

87-232-16040

CARIBOO-BELL PROJECT
1986 GEOCHEMICAL, GEOPHYSICAL AND DRILLING REPORT
ON THE
BJ, BOOTJACK, CB AND POLLEY MINERAL CLAIMS
CARIBOO MINING DIVISION
NTS 93A/12E
Lat. 52°33'N Long. 121°38'W

4/78

APPENDIX 1, 2 and 4

VOLUME III OF III

FILMED

PART 3 OF 3

February 15, 1987

By: Ken McNaughton, M.A.Sc., P. Eng.
Project Geologist

**GEOLOGICAL BRANCH
ASSESSMENT REPORT**

16,040

LIST OF FIGURES

		<u>PAGE NO.</u>
A	Compilation Map	iv
1	Property and Claim Location	3
1A	Claim and Grid Location	4
2	Locations of Surveyed Drill Holes	21
3	N-S Section Through High Grade Zone	22
4	to E-W Section Through High Grade Zone	23
5-7	Soil Geochemistry Copper	Volume II
8-10	Soil Geochemistry Gold	Volume II
11	Total Field Magnetic Contours	Volume II
12	VLF-EM Fraser	Volume II
13, 14	VLF-EM Profiles	Volume II
15, 16	Geophysical Interpretation	Volume II
17 to 19	Geology	Volume II

LIST OF TABLES

1	Rotary Drill Hole Locations	19
2	Significant Drill Intersections	20

LIST OF APPENDICES

1	Mineral Titles	Volume III
2	Geophysical Interpretation Report	Volume III
3	Drill Logs, Rotary Drill Holes R-86-19 to 40	Volume I
4	Assay Certificates	Volume I, III
5	Check Assay Certificates	Volume I

APPENDIX I
MINERAL TITLES

CLAIM	UNITS	RECORD NO.	RECORD DATE	EXPIRY DATE
BJ 1	1	28639K	13/08/64	13/08/92
BJ 2	1	28640K	13/08/64	13/08/92
BJ 3	1	28641K	13/08/64	13/08/92
BJ 4	1	28642K	13/08/64	13/08/92
BJ 5	1	28643K	13/08/64	13/08/92
BJ 6	1	28644K	13/08/64	13/08/92
BJ 7	1	28645K	13/08/64	13/08/92
BJ 8	1	28646K	13/08/64	13/08/92
BJ 9	1	28647K	13/08/64	13/08/92
BJ 10	1	28648K	13/08/64	13/08/92
BJ 11	1	28649K	13/08/64	13/08/92
BJ 12	1	28650K	13/08/64	13/08/92
BJ 13	1	28651K	13/08/64	13/08/92
BJ 14	1	28652K	13/08/64	13/08/92
BJ 15	1	28653K	13/08/64	13/08/92
BJ 16	1	28654K	13/08/64	13/08/92
BJ 17	1	28655K	13/08/64	13/08/92
BJ 18	1	28656K	13/08/64	13/08/92
BJ 19	1	28657K	13/08/64	13/08/92
BJ 20	1	28658K	13/08/64	13/08/92
BJ 21	1	28659K	13/08/64	13/08/92
BJ 22	1	28660K	13/08/64	13/08/92
BJ 23	1	28661K	13/08/64	13/08/92
BJ 24	1	28662K	13/08/64	13/08/92
BJ 25	1	28663K	13/08/64	13/08/92
BJ 26	1	28664K	13/08/64	13/08/92
BJ 27	1	28665K	13/08/64	13/08/92
BJ 43	1	28978M	15/09/64	15/09/92
BJ 45	1	28980M	15/09/64	15/09/92
BJ 47	1	28982M	15/09/64	15/09/92
BJ 49	1	28984M	15/09/64	15/09/92
BJ 50	1	28985M	15/09/64	15/09/92
BJ 51	1	28986M	15/09/64	15/09/92
BJ 52	1	28987M	15/09/64	15/09/92
BJ 53	1	28988M	15/09/64	15/09/92
BJ 54	1	28989M	15/09/64	15/09/92
BJ 55	1	28990M	15/09/64	15/09/92
BJ 56	1	28991M	15/09/64	15/09/92

CLAIM	UNITS	RECORD NO.	RECORD DATE	EXPIRY DATE
BJ 57	1	28992M	15/09/64	15/09/92
BJ 58	1	28993M	15/09/64	15/09/92
BJ 59	1	28994M	15/09/64	15/09/92
BJ 60	1	28995M	15/09/64	15/09/92
BJ 63	1	28996M	15/09/64	15/09/92
BJ 64	1	28997M	15/09/64	15/09/92
BJ 69	1	29002M	15/09/64	15/09/92
BJ 113	1	29046M	15/09/64	15/09/92
BJ 114	1	29047M	15/09/64	15/09/92
BJ 115	1	29048M	15/09/64	15/09/92
BJ 116	1	29049M	15/09/64	15/09/92
BJ 117	1	29050M	15/09/64	15/09/92
BJ 118	1	29051M	15/09/64	15/09/92
BJ 119	1	29052M	15/09/64	15/09/92
BJ 120	1	29053M	15/09/64	15/09/92
BJ 121	1	29054M	15/09/64	15/09/92
BJ 122	1	29055M	15/09/64	15/09/92
BJ 123	1	29056M	15/09/64	15/09/92
BJ 124	1	29057M	15/09/64	15/09/92
BJ 125	1	29058M	15/09/64	15/09/92
BJ 126	1	29059M	15/09/64	15/09/92
BJ 130	1	29063M	15/09/64	15/09/92
BJ 132	1	29065M	15/09/64	15/09/92
Bootjack 1 Fr.	1	29851G	02/06/65	02/06/92
Bootjack 2 Fr.	1	29852G	02/06/65	02/06/92
BJ 144	1	31175P	12/11/65	12/11/92
BJ 146	1	31177P	12/11/65	12/11/92
BJ 148	1	31179P	12/11/65	12/11/92

CLAIM	UNITS	RECORD NO.	RECORD DATE	EXPIRY DATE
CB 1	20	3401 (5)	04/05/81	04/05/88
CB 4	8	3402 (5)	04/05/81	04/05/88
CB 5	20	3403 (5)	04/05/81	04/05/88
CB 6	15	3404 (5)	04/05/81	04/05/88
CB 7	20	3405 (5)	04/05/81	04/05/88
CB 8	8	3406 (5)	04/05/81	04/05/88
CB 9	20	3407 (5)	04/05/81	04/05/88
CB 10	20	3408 (5)	04/05/81	04/05/88
CB 11	4	3409 (5)	04/05/81	04/05/88
CB 13	(20)	3410 (5)	04/05/81	04/05/86
CB 14	20	3411 (5)	04/05/81	04/05/88
CB 15	20	3412 (5)	04/05/81	04/05/88
CB 16	20	3413 (5)	04/05/81	04/05/88
CB 17	(20)	3414 (5)	04/05/81	04/05/85
CB 18	(20)	3415 (5)	04/05/81	04/05/86
CB 19	20	3416 (5)	04/05/81	04/05/88
CB 20	20	3417 (5)	04/05/81	04/05/88

CLAIM	UNITS	RECORD NO.	RECORD DATE	EXPIRY DATE
Polley 3	1	3330 (4)	09/04/81	09/04/87
Polley 4	1	3331 (4)	09/04/81	09/04/87
Polley 5	1	3332 (4)	09/04/81	09/04/87
Polley 6	1	3333 (4)	09/04/81	09/04/87
Polley 7	1	3334 (4)	09/04/81	09/04/87
Polley 8	1	3335 (4)	09/04/81	09/04/87
Polley 9	1	3336 (4)	09/04/81	09/04/87
Polley 10	1	3337 (4)	09/04/81	09/04/87
Polley 11	1	3338 (4)	09/04/81	09/04/87
Polley 12	1	3339 (4)	09/04/81	09/04/87
Polley 13	1	3340 (4)	09/04/81	09/04/87
Polley 14	1	3341 (4)	09/04/81	09/04/87
Polley 15	1	3342 (4)	09/04/81	09/04/87
Polley 16	1	3343 (4)	09/04/81	09/04/87
Polley 17	1	3344 (4)	09/04/81	09/04/87
Polley 18	1	3345 (4)	09/04/81	09/04/87
Polley 19	1	3346 (4)	09/04/81	09/04/87
Polley 20	1	3347 (4)	09/04/81	09/04/87
Polley 21	1	3348 (4)	09/04/81	09/04/87
Polley 22	1	3349 (4)	09/04/81	09/04/87

APPENDIX II
GEOPHYSICAL INTERPRETATION
BY
ED ROCKEL
OF
INTERPRETEX RESOURCES

CARIBOO BELL GEOPHYSICAL INTERPRETATION
OF
VLF EM, MAGNETIC AND INDUCED POLARIZATION SURVEYS

1. SURVEY SPECIFICATIONS

1.1 Survey Parameters

- survey line separation - 100 and 200 meters as per plan map
- survey station spacing - 12.5 meters for all VLF EM and magnetic survey
 - 25 meters for all induced polarization survey
- horizontal control - lines were surveyed by compass and hip chain with estimated slope corrections
 - semi-recoverable stations were located using felt pen markings on flagging tied to vegetation
 - grid tied in to base line 5000W and to lakes
- baseline direction - north-south
- survey lines were perpendicular to the base line
- readings from Seattle VLF transmitter were recorded on all lines
- readings from Cutler VLF transmitter were also recorded on lines 7500N to 7900N and baseline 5000N
- Induced polarization and resistivity surveys were carried out in three localized areas within the main survey area as follows:
 - Area 9300N to 9800N on lines 9300N, 9500N, 9700N & 9800N
 - Area 10600N to 11200N on lines 10600N, 10800N, 11000N & 11200N
 - Area 11300N to 11700N on lines 11300N, 11400N, 11500N, 11600N & 11700N
- survey totals:

	VLF EM	
	Magnetic	Seattle Cutler
Induced Polarization	179.45 km.	172.05 km. 27.625 km.
13.250 km.		

1.2 Equipment Parameters

VLF Electromagnetic Survey

- Geonics EM-16 used for all survey
- transmitting stations - Seattle, Washington
 - Cutler, Maine
- in-phase (dip angle) and out-of-phase (quadrature) components measured in percent at each station
- direction faced: Seattle - easterly
 - Cutler - northerly, southerly on base line

Total Field Magnetic Survey

- measured total magnetic field in gammas using EG & G G-816 proton precession magnetometer
- magnetic variations controlled by EG & G G-856 automatic magnetic base station recording every 30 seconds
- instrument accuracy +/- 1 gamma
- station repeatability better than +/- 3 gammas

Induced Polarization Survey

- Hunttec Mk II 7.5 kilowatt transmitter
- Hunttec Mk IV time domain receiver
- Interpretex Resources Ltd. 7.5 Kw. engine alternator system
- apparent chargeability measured in milliseconds
- primary voltage measured in millivolts
- apparent resistivity determined in ohm-meters
- dipole spacing a = 25 meters, n = 1 to 6
- pole-dipole method with pole westerly and dipole easterly

1.3 Equipment Specifications - see appendix

2. DATA

2.1 Calculations

VLF Electromagnetic Survey

Fraser Filter values (after Fraser, 1969, reference 1.) were calculated for in-phase readings from the Seattle transmitter for all lines in the area.

Induced Polarization Survey

Apparent resistivity values were calculated using the formula;

$$Pa = 2n(n + 1)PI*a*(V/i)$$

- where: n = "n" value of 1 to 6
PI = 3.14
a = electrode separation (meters)
V = observed voltage (millivolts)
i = observed current (amps)
* = "multiplied by"

Metal Factor values were computed using the formula;

$$MF = (Ma/Pa)*1000$$

- where: Ma = apparent chargeability
Pa = apparent resistivity
* = "multiplied by"

Total Field Magnetic Survey

Total field magnetic readings were individually corrected for variations in the earth's magnetic field using magnetic base station values recorded at the same time. The effects of changes in magnetic content of operator's clothing or different batteries used in the magnetometer were controlled by re-occupying operator field base stations at the beginning and end of each day during the survey. An "operator adjust" correction was then applied where applicable.

2.2 Presentation

- Apparent chargeability Fraser Filter values, apparent resistivity Fraser Filter values, magnetic readings and VLF EM Fraser Filter values within localized IP survey areas are presented as computer contours at a scale of 1:5000. Apparent chargeability Fraser Filter values and magnetic readings are presented in the form of 3D plots for visual aids
- VLF EM in-phase readings plus calculated Fraser Filter values are presented in an appendix of this report in the form of tables showing values located with respect to line number and station number
- VLF EM in-phase and out-of-phase readings are presented in profile form on a grid plan map at a scale of 1:5000
- VLF EM Fraser Filter contours (positive values only) are presented on a grid plan map at a scale of 1:5000
- operator adjust values used in magnetic data corrections are presented with respect to operator name and survey date in an appendix of this report
- magnetic field and base station values are presented in the form of tables on "Total Field Magnetic Data Corrections Worksheets" in an appendix of this report
- total field magnetic values were computer contoured at 250 gamma intervals on a grid plan map at a scale of 1:5000
- IP data and calculated values are presented in an appendix of this report as "Induced Polarization Data Calculation Worksheets"
- IP data are presented as contoured pseudosections on pseudosection maps at a scale of 1:1250
- IP anomalies are presented on the pseudosection maps and Geophysical Interpretation Map as rectangles
- a geophysical interpretation is presented on a Geophysical Interpretation Map at a scale of 1:5000.

3. INTERPRETATION

3.1 Discussion of Results

On this project topography varied from flat to severe in a few cases, thus at times a topographic effect is evident in some VLF EM data in the form of a positive bias in the readings when facing up hill and a negative when facing down hill. Most of the effect of topography is filtered out when the Fraser Filter is applied to the in-phase data. Both the filtered values and VLF EM profiles were used in this report to interpret the VLF EM data on all lines. Character matching and contours provided the means for continuing conductive trends. Overburden was not considered a problem in this region because of the shallow depth as evidenced by the prevalence of float boulders and some outcrop.

VLF EM data was accumulated using both the Seattle and Cutler transmitting stations until it was recognized that the Cutler data was redundant when using station intervals of 12.5 meters on east-west lines with line separations of 100 and 200 meters. In order to properly utilize Cutler VLF EM values additional stations would have been required between survey lines in order to provide sufficient data

density for meaningful results. Therefore VLF EM survey was continued at 12.5 meter station intervals using only the Seattle transmitting station. Except for base line data, Cutler results were not utilized.

Magnetic data were generally active in most of the area. Station to station variations within 12.5 meters were often of the order of 100 gammas or more and in some cases of the order of 500 gammas or more. In the present area a total of five different magnetometer operators using two different G-816 magnetometers were employed over a period of approximately three months to gather magnetic data. For this reason operator adjust values can be seen to be variable and, in some cases, higher than normally expected. Total field values ranged from around 54,000 gammas to over 69,000 gammas in magnetically active areas.

Induced polarization data were noise free except in minor cases where poor contact reduced signal to noise ratio and required extra time and repeated readings in order to obtain reliable values. Chargeability readings ranged from less than 3.0 milliseconds to greater than 100 milliseconds (single point) with anomalous threshold considered to be 12.5 milliseconds. In some cases negative IP effects can be seen adjacent to positive anomalies. Repeated check readings demonstrated that the negative readings were valid. All relatively large chargeability readings (168 mS., 93 mS., etc.) which can be seen on some survey lines have been checked and duplicated in the field and are therefore considered to be valid.

Apparent resistivity values ranged from under 100 ohm-meters to over 4,000 ohm-meters. Topographic influence was not readily apparent in resistivity data in this region.

3.2 Conclusions

3.2.1 General

Geophysical surveys have delineated a network of structural features, shown regions which probably contain significant amounts of magnetite and/or pyrrhotite and have outlined localized areas which contain anomalous amounts of disseminated sulphides.

Major structural trends seem to strike towards the northwest in the northern half of the area and more northerly or possibly slightly northeast in the southern half. In addition to the above structure, a cross cutting fault has been interpreted, in the vicinity of line 8400N, sub-parallel to survey lines. The fault was interpreted on the basis of VLF EM conductor offsets and magnetic contour perturbations. No VLF EM response was observed due to the shallow angle of incidence where survey lines crossed the interpreted position of the postulated fault.

3.2.2 VLF Electromagnetic Survey

The VLF EM survey, with a station interval of 12.5 meters, delineated a
...5

multitude of EM anomalies and resulted in the interpretation of a large number of conductor systems. Generally the stronger and longer strike length conductors are found in the north half of the area. Based on prior knowledge, there does not seem to be a direct relationship between VLF EM conductivity and economically mineralized zones, although some appear to pass through mineralized areas. Most conductivity is believed to represent a network of interrelated structure such as primary and secondary complimentary faults. In the case of stronger systems, the stronger VLF EM anomalies may result from the presence of sulphides within and controlled by the structural features. Some conductor systems appear to show strike offsets or abrupt changes in direction. This may be due to cross cutting faults which are at shallow angles with respect to survey lines and therefore can not be detected by the present VLF EM survey. An example of a cross cutting fault is interpreted on the Geophysical Interpretation Map as an "inferred fault zone" and is labeled "F".

Certain conductor systems, deemed important, have been labeled for more detailed discussion. Unlabeled conductors and anomalies are probably due to minor structure or surface material such as clay layers. Weak short features are probably all due to overburden conductivity or tight wet fractures in bedrock.

Conductor "A"

The longest conductor system in this area has been labeled "A". This system correlates with a long magnetic lineation and is interpreted as a conductive regional fault. Various anomalies along the system show moderate to strong response. These stronger anomalies probably reflect the presence of more conductive material within the fault zone with possibly a greater depth extent. Near the southern extremity of "A" the strike of the system changes towards a more southerly direction and then appears to break up into shorter northwest trending conductive zones before ending, possibly due to a transition into different rock type and perhaps different force directions. Magnetic contour trends also show the same southward change.

In the vicinity of survey lines 9700N to 10600N conductor "A" appears to split into two parallel zones. The weaker offshoot conductor is labeled "A1" and partially follows a magnetic lineation slightly west of "A". This split probably reflects a double break or two conductive edges of a wide fault zone. Another nearly parallel conductor, labeled "A2", is also believed to be related to the main regional fault. At approximately line 9400N a third split seems to occur with conductor "A3" diverging more towards the north, away from the main zone "A". Conductor "A3" follows a magnetic trend near and sub-parallel to base line 5000N. A number of strong anomalies in "A3" indicate that this system may represent a significant break with portions of the structure possibly containing sulphide mineralization. An interpretation of a relationship between "A", "A1", "A2" and "A3" suggests that the postulated regional fault ("A") widens towards the north and ultimately splits apart into a number of sub-parallel and diverging fault zones while in the south the fault tightens up and finally ends as a narrow discontinuous feature.

Conductor "B"

The multiple conductor system "B" is also interpreted as a regional structural feature although it is discontinuous, has indefinite magnetic support and, at one point, becomes non-conductive. System "B" does, however, contain a number of strong and therefore noteworthy anomalies. Although the conductivity-thickness product (conductance) is only moderate, these anomalies may represent long (of the order of 300 meters or more) and deeply extending narrow zones of sulphide mineralization within the faults. A northwesterly trending conductor, labeled "B1", is coincident with a subtle magnetic lineation, contains some moderate and strong anomalies and appears to join the main "B" group of conductors, suggesting a related structural feature possibly containing sulphides.

Conductor "C"

System "C" appears to be a complex series of conductors, many with strong anomaly amplitudes. Anomalies in system "C", between approximately lines 9000N and 9600N, show higher conductance than on most other conductor systems in the area. This is believed to represent a zone of conductive massive sulphides which is wider than in other cases. The discontinuous nature of the conductive trends and what appear to be intersecting faults, or fault zones which seem to splay off from the main trend, may mean that larger cavities were formed in this area resulting in accumulation of wider zones of conductive mineralization. EM profile character has suggested an unusual strike change from the northwesterly direction, resulting in the interpretation of conductors "C1" and "C2" striking towards the northeast. Although conductor "C3" does not connect with "C", its similar character and strike direction suggest it is related geologically. As conductor "C1" continues northeast from "C" profile character again indicates a swing back towards the northwest, to nearly parallel, and perhaps link up with conductor "A". This phenomenon again suggests that most of the conductors in this area represent a network of conjugate structural features.

3.2.3 Total Field Magnetic Survey

The total field magnetic survey in the present area has shown two general magnetic environments, one relatively inactive and the other more active. A change in magnetic background in the vicinity of line 7300N is roughly delineated on the interpretation map and shown as "-M-". The magnetic background level in the southern portion of the survey area (south of the "-M-" line) is lower than in the north up until another level change (also shown as "-M-") again takes place, back down to a lower level. A small "active area" is outlined (with the symbol "-M-") in the northeast between lines 9800N and 10800N.

Both the level of magnetism and the general magnetic activity (the number of magnetic anomalies present and their strength) in the "active areas" are greater than in the "low level" areas. This probably indicates a rock type change from more magnetic rock containing more magnetite in the higher magnetic background areas, to less magnetic rock

containing fewer occurrences of magnetic minerals, such as magnetite, in the less magnetically active areas. (Large magnetic anomalies within the "active" area are believed to be due to local occurrences of magnetite.)

An unusual magnetic low, unique in this survey area, is found within the interpreted magnetically "lower level" region, on line 6800N in the vicinity of 4500W to 4800W. Model studies suggest that the magnetic low feature is caused by natural remanent magnetism with a direction of magnetization approximately opposite to the present earth's magnetic field. Study of the large amplitude and curve shape of the negative anomaly indicates, through model calculations, that the cause could be a narrow ultrabasic dyke or rock unit containing magnetite, trending parallel to line 6800N from approximately 4550W to about 4800W. Assuming that the model used is reasonable, the depth seems to vary from near surface (of the order of 10 meters or less) near 4800W, to about 50 meters around 4700W and then to perhaps 25 meters in the vicinity of 4550W.

A single line magnetic high anomaly, also in the "low level" region is evident in the north part of the survey area on line 12200N from 5600W to 5700W. This anomaly is probably due to a local near surface occurrence of magnetic material related to magnetic anomalies within the "active areas".

3.2.4 Induced Polarization and Resistivity Survey

Negative IP effects can be seen on a few lines, within the areas surveyed. These negative values are possible and not abnormal near bodies of limited lateral extent. The negative response is due to the vectorial electrical field relationships of a polarizable body during the polarizing (current on) and depolarizing (current off) cycles of current transmission and the position of receiver electrodes with respect to the target body. (reference 2.)

Little use was made of metal factor values in the present interpretation because of the favourable relationship between apparent chargeability highs and apparent resistivity highs rather than the normal inverse relationship. Metal factor calculations are designed to enhance the inverse relationship between apparent chargeability and apparent resistivity.

The three localized areas in which IP survey was carried out are discussed in more detail below:

Area 9300N to 9800N

This region was surveyed first to determine an IP signature over known disseminated sulphide mineralization. Line 9700N was extended to cover a barren pyrite occurrence, in the vicinity of 5700W to 5900W, to see if a difference in signature between the barren pyrite and gold bearing mineralization could be observed. It was found that although both sulphide occurrences gave a good apparent chargeability response, the

barren pyrite zone high chargeability was accompanied by an apparent resistivity low, whereas anomalous chargeability from the economic mineral occurrence was associated with an apparent resistivity high. It was also noted that the economic zone of interest also correlated with a large magnetic high anomaly. Magnetite is believed to be responsible for the increase in resistivity in the economically interesting zone containing high apparent chargeability values. A simplified exploration rule (possibly over-simplified) would then be to place a higher priority on chargeability anomalies which are accompanied by higher than background apparent resistivity and a lower priority on apparent chargeability values which correspond with apparent resistivity lows.

Using the above evaluation rule the following locations are given a high priority for follow-up exploration: (along with a rudimentary interpretation based on model study theoretical pseudosection contours and a simplified assignment of "rank" within the high priority targets)

LINE #	LOCATION (westing)	APPROX. DEPTH (meters)	ATTRIBUTE	POSS. GEOMETRY	RANK
9300N	5100 - 5175	50 - 75	weak	unstructured zone	3
"	5750 - 5760	> 50	weak	" "	3
9500N	5075 - 5125	surface	moderate	dyke-like - narrow	3
"	5150 - 5200	"	"	thin layer zone	2
"	5325 - 5375	approx. 50	weak	dyke-like dips W?	3
"	5750 - 5800	surface	moderate	unstructured zone	2
9700N	5050 - 5075	> 25	weak	undefined	3
"	5250 - 5375	surface	strong	unstructured zone	1
"	5650 - 5675	"	strong	dyke-like dips W?	1
9800N	5025 - 5050	approx. 25	weak	undefined	3
"	5300 - 5450	> 25	weak	unstructured zone	3
"	5450 - 5500	surface	moderate	thin layer zone	2
"	5550 - 5600	approx. 25	weak	unstructured zone	2

Area 10600N to 11200N

Only three anomalies (using an apparent chargeability anomalous threshold of 12.5 milliseconds) were observed in this IP investigation area. All three apparent chargeability anomalies correspond with apparent resistivity lows and thus have not been listed as priority targets.

Area 11300N to 11700N

All of the strong apparent chargeability anomalies in this IP investigation area have nearby negative chargeability values. This suggests that these anomalies are of limited lateral extent as per previous discussion.

The following apparent chargeability anomaly locations are considered targets for economic mineralization:

LINE #	LOCATION (westing)	APPROX. DEPTH (meters)	ATTRIBUTE	POSS. GEOMETRY	RANK
11300N	5225 - 5250	25 - 50	weak	small unstructured	3
11400N	5250 - 5300	surface	"	thin layer zone	3
11600N	4800 - 4875	< 25	"	dyke-like perp dip?	3
11700N	4850 - 4900	> 50	strong	small unstructured	1

Other strong apparent chargeability anomalies in this region are believed to contain sulphide mineralization but were not listed as priority targets due to the lack of corresponding higher apparent resistivity.

4. RECOMMENDATIONS

VLF EM conductor systems interpreted as structure may be genetically related to economically mineralized zones and therefore the stronger conductors are recommended for follow-up both to determine mineral content and to explore their relationship to larger zones of disseminated gold bearing sulphides.

Intense magnetic high anomalies, interpreted as magnetite, appear to be related to gold mineralization and therefore any significant magnetic high anomalies which have not been adequately explored are recommended for detailed IP survey coverage to determine if disseminated sulphide mineralization exists. The unusual magnetic low, found mainly on line 6800N should be investigated to confirm the cause of the large magnitude of the magnetic low and to determine if significant mineralization exists.

Generally the higher priority IP targets, defined above in Section 3.2.4, are considered important for follow-up exploration. These higher priority targets have been given a "rank" to further define priorities for continued work. The apparent chargeability anomalies not listed, due to the absence of coincident higher apparent resistivity values, are also considered targets for additional exploration pending support from favourable geochemical and geological information.


REFERENCES

1. Fraser, D.C., 1969. Contouring of VLF EM Data, Geophysics, Vol. 34, No. 6, December, 1969, Tulsa, Oklahoma.
2. Sumner, J.S., 1976. Principals of Induced Polarization for Geophysical Exploration, Elsevier North-Holland Inc., New York, N.Y.
3. Sharma, P.V., 1976. Geophysical Methods in Geology, Elsevier Scientific Publishing Company, Amsterdam, The Netherlands
4. Telford, W.M., 1976. Applied Geophysics, Cambridge University Press, Cambridge, England

Respectfully Submitted


INTERPRETEX RESOURCES LTD.

Vancouver, British Columbia

A handwritten signature in black ink, appearing to read 'E.R. Rockel', written over a horizontal line.

E.R. ROCKEL

Consulting Geophysicist




CERTIFICATE

I, Edwin Ross Rockel, Geophysicist of Vancouver, British Columbia, Canada, hereby certify that:

1. I received a B.Sc. degree in Geophysics from the University of British Columbia in 1966.
2. I have been practising my profession since graduation.
3. I am a Professional Geophysicist registered in the Province of Alberta.
4. I am a Professional Engineer registered in the Province of Saskatchewan.
5. I hold no direct or indirect interest in, nor expect to receive any benefits from, the mineral property or properties described in this report.
6. This report may be used for the development of the property, provided that no portion will be used out of context in such a manner as to convey meanings different from that set out in the whole.
7. Consent is hereby given to the company for which this report was prepared to reproduce the report or any part of it for the purposes of development of the property, or facts relating to the raising of funds by way of a prospectus and/or statement of material facts.

Date: Dec. 31, 1986

Signed: _____



Vancouver,
British Columbia

Edwin Ross Rockel
B.Sc., P.Geoph., P. Eng.

GEOPHYSICAL PERSONNEL

PERSONNEL

The following personnel worked on the property and/or were engaged in supervision for all or part of the days noted (includes mobilization and demobilization):

<u>Name</u>	<u>Position</u>	<u>Dates</u>
E.R. Rockel Richmond, B.C.	Consulting Geophysicist	Sept. 4 - 9, 1986 Oct. 14 - Nov. 2, 1986
T.R. Matich Surrey, B.C.	Geophysicist	Aug. 6 - Sept. 9, 1986 Oct. 14 - Nov. 2, 1986
H.M. Rockel Richmond, B.C.	Data Person	Oct. 14 - Nov. 2, 1986
J.A. Martin Vancouver, B.C.	Geophysical Technician	Aug. 6 - 12, 1986 Aug. 24 - Sept. 9, 1986 Oct. 14 - Nov. 2, 1986
G.J. McPherson Surrey, B.C.	Geophysical Technician	Aug. 24 - Sept. 9, 1986 Oct. 14 - Nov. 2, 1986
D.J. Sedgwick North Delta, B.C.	Geophysical Technician	Aug. 24 - Sept. 9, 1986 Oct. 14 - Nov. 2, 1986
L.A. Wilkinson Port Coquitlam, B.C.	Geophysical Assistant	Aug. 13 - 19, 1986
T.D. Plant Likely, B.C.	Geophysical Assistant	Oct. 14 - Nov. 2, 1986

The following personnel were involved in data preparation or reporting of the project for part or all of the days noted:

<u>Name</u>	<u>Position</u>	<u>Dates</u>
E.R. Rockel Richmond, B.C.	Consulting Geophysicist	Sept. 11, 12, 14 - 16, 18, 19, 22, 25, 26, 29, 30, Oct. 6, 8, Nov. 14 - 16, 18, 20 - 23, 25, 26, 30, Dec. 1, 4, 6 - 12, 14, 15, 17, 21, 23, 24, 29 - 31, 1986
T.R. Matich Surrey, B.C.	Geophysicist	Sept. 12, 15 - 19, 1986

APPENDIX 4
ASSAY CERTIFICATES

VANGEOCHEM LAB LIMITED

MAIN OFFICE: 1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604)986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND
 IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE. ND= NOT DETECTED. -- NOT ANALYZED. *AU= AQUA REGA/AAS

COMPANY: E & B EXPLORATIONS REPORT#: 860434PA DATE RECEIVED: 86/09/03
 ATTENTION: L.SALEKEN & M.TINDALL JOB#: 860434 DATE COMPLETED: 86/09/22
 PROJECT: 5061-CB P0#5589 INVOICE#: 860434NA COPY SENT TO: VANCOUVER OFFICE

ANALYST W. P. P. P.

PAGE 1 OF 8

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L106N 70+25W	.1	ND	35	19	30	408	4.67	2	22	15	111
L106N 70+50W	.1	ND	20	50	62	1330	7.18	7	48	38	264
L106N 70+75W	.1	ND	15	15	28	322	4.01	1	19	15	107
L106N 71+00W	.1	7	5	5	22	57	3.13	1	5	4	51
L106N 71+25W	.1	ND	30	11	27	153	4.15	ND	17	10	119
L106N 71+50W	.1	ND	30	16	27	405	4.77	1	16	14	102
L106N 71+75W	.1	3	30	9	21	111	3.54	1	8	13	103
L106N 72+00W	.1	ND	30	12	23	199	3.77	1	13	15	116
L106N 72+25W	.1	8	35	20	24	633	4.75	1	21	19	119
L106N 72+50W	.1	ND	30	18	30	405	4.32	1	20	16	99
L106N 72+75W	.1	3	20	16	29	356	4.25	2	18	18	94
L106N 73+00W	.1	ND	5	11	23	282	2.15	ND	14	13	62
L108N 70+25W	.1	ND	25	22	28	448	4.90	3	19	12	116
L108N 70+50W	.1	ND	15	12	23	92	3.87	1	11	11	231
L108N 70+75W	.1	8	10	6	20	43	3.12	1	6	10	92
L108N 71+00W	.1	ND	5	10	21	121	4.12	ND	10	8	171
L108N 71+25W	.1	ND	15	12	22	61	5.12	ND	7	9	138
L108N 71+50W	.1	ND	40	22	24	763	4.95	2	20	16	113
L108N 71+75W	.1	3	20	16	24	455	4.10	1	16	15	99
L108N 72+00W	.1	10	50	13	21	354	3.83	1	14	13	89
L108N 72+25W	.1	6	15	14	24	233	3.85	2	20	18	78
L108N 72+50W	.1	7	30	12	27	210	3.47	1	18	16	85
L108N 72+75W	.1	9	20	14	26	296	3.70	1	18	20	84
L108N 73+00W	.1	5	10	13	25	293	3.62	1	15	17	82
L108N 73+25W	.1	7	20	13	29	135	2.62	1	17	20	66
L108N 73+50W	.1	11	10	12	27	57	2.97	1	16	14	66
L108N 73+75W	.1	14	10	6	19	43	2.11	1	9	15	55
L108N 74+00W	.1	10	15	6	15	59	1.63	ND	8	19	45
L110N 70+25W	.1	3	5	9	27	157	2.38	ND	15	15	57
L110N 70+50W	.1	ND	20	12	23	375	3.59	1	15	13	130
L110N 70+75W	.1	ND	20	10	25	3150	3.24	2	24	2	78
L110N 71+00W	.1	ND	5	9	29	187	3.41	ND	12	4	155
L110N 71+25W	.1	ND	20	11	24	140	4.54	2	10	7	176
L110N 71+50W	.1	ND	25	7	24	4061	2.52	2	20	ND	60
L110N 71+75W	.1	ND	15	23	40	2914	5.48	2	38	16	136
L110N 72+00W	.1	ND	10	8	20	1820	2.54	1	16	ND	62
L110N 72+25W	.1	ND	20	16	29	273	5.12	ND	17	13	254
L110N 72+50W	.1	ND	20	12	30	147	4.99	ND	12	9	222
L110N 72+75W	.1	5	30	12	24	207	4.25	2	13	12	106
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L110N 73+00W	.1	ND	ND	28	34	903	5.41	2	27	30	163
L110N 73+25W	.1	5	145	18	29	465	5.09	1	23	23	121
L110N 73+50W	.1	ND	20	13	27	270	5.37	2	17	18	167
L110N 73+75W	.1	ND	10	20	31	398	4.29	4	16	18	177
L110N 74+00W	.1	5	5	18	27	305	4.99	3	15	19	146
L112N 70+25W	.1	ND	25	16	27	487	5.30	2	16	16	164
L112N 70+50W	.1	ND	20	20	27	1129	4.65	2	22	15	123
L112N 70+75W	.1	ND	15	15	25	416	5.33	1	16	13	151
L112N 71+00W	.1	4	5	12	20	1273	3.45	4	18	7	93
L112N 71+25W	.1	ND	20	23	33	1127	5.58	2	27	19	154
L112N 71+50W	.1	ND	15	13	31	2268	4.01	1	31	15	98
L112N 71+75W	.1	ND	15	27	52	1572	6.50	3	46	29	189
L112N 72+00W	.1	ND	20	15	36	455	4.25	1	28	14	142
L112N 72+25W	.1	ND	20	16	38	466	4.54	1	30	15	143
L112N 72+50W	.1	ND	10	9	31	299	3.24	1	24	6	116
L112N 72+75W	.1	4	30	16	44	468	3.72	2	25	13	76
L112N 73+00W	.1	4	25	10	29	234	4.07	1	11	13	117
L112N 73+25W	.1	ND	20	11	28	165	4.74	1	10	13	172
L112N 73+50W	.1	4	20	3	13	2102	1.60	3	14	ND	31
L112N 73+75W	.1	4	20	3	14	1911	1.58	3	20	ND	32
L112N 74+00W	.1	ND	10	12	30	177	4.89	4	23	14	192
L114N 44+75W	.1	ND	5	11	38	84	3.15	ND	26	8	60
L114N 45+00W	.1	ND	5	11	51	42	3.77	ND	22	7	78
L114N 45+25W	.1	ND	ND	14	63	45	4.02	ND	30	10	93
L114N 45+50W	.1	ND	ND	13	68	36	4.10	ND	29	7	103
L114N 45+75W	.1	ND	ND	12	78	45	4.34	ND	30	11	79
L114N 46+00W	.1	ND	ND	14	90	52	4.87	ND	33	9	69
L114N 46+25W	.1	ND	ND	14	71	49	4.27	ND	30	11	75
L114N 46+50W	.1	ND	ND	14	67	58	4.55	ND	29	12	66
L114N 46+75W	.1	14	10	11	28	158	3.22	1	19	17	56
L114N 47+00W	.1	5	10	11	45	79	3.40	ND	24	9	66
L114N 47+25W	.1	ND	5	10	63	26	3.70	ND	21	8	102
L114N 47+50W	.1	ND	10	12	67	44	3.83	ND	34	12	77
L114N 47+75W	.1	4	5	8	50	30	3.11	ND	18	12	59
L114N 48+00W	.1	21	5	6	30	13	2.12	2	12	24	44
L114N 48+25W	.1	5	5	15	62	80	3.77	ND	42	32	76
L114N 48+50W	.1	11	5	12	41	100	3.32	1	23	30	95
L114N 48+75W	.8	14	190	29	22	5302	4.67	9	14	50	232
L114N 49+00W	.2	10	100	25	34	2768	5.22	6	22	39	194
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L114N 49+25W	.4	7	20	15	44	318	3.88	2	25	17	89
L114N 49+50W	.1	ND	15	12	46	137	3.52	1	26	15	61
L114N 49+75W	.1	8	10	10	36	100	3.08	1	19	16	79
L114N 70+25W	.4	ND	5	12	27	1366	3.31	2	26	15	86
L114N 70+50W	.1	ND	35	12	22	372	3.92	1	20	14	106
L114N 70+75W	.1	4	35	13	18	371	3.80	1	12	16	93
L114N 71+00W	.1	ND	20	11	19	254	3.87	1	12	14	162
L114N 71+50W	.1	ND	25	14	23	494	4.02	1	17	12	138
L114N 71+75W	.1	ND	20	12	22	405	4.00	1	14	13	119
L114N 72+00W	.1	3	55	16	24	650	4.25	1	18	11	75
L114N 72+25W	.1	ND	40	16	24	560	3.90	1	19	14	92
L114N 72+50W	.1	ND	35	19	28	812	4.50	2	21	14	96
L114N 72+75W	.1	4	45	17	27	661	4.34	2	21	13	72
L114N 73+00W	.1	3	25	13	23	1235	3.55	4	18	10	77
L114N 73+25W	.1	ND	15	15	25	1598	3.59	3	22	9	101
L114N 73+50W	.1	ND	15	18	33	1023	4.62	2	25	11	112
L114N 73+75W	.1	ND	15	15	23	702	3.65	3	20	11	121
L114N 74+00W	.1	ND	20	13	23	799	3.46	2	17	7	127
L116N 45+75W	.1	7	10	17	39	109	3.83	1	25	10	67
L116N 46+00W	.1	6	5	11	34	449	2.77	1	29	7	81
L116N 46+25W	.1	4	5	13	38	56	3.31	1	28	14	69
L116N 46+50W	.1	9	10	12	30	83	3.01	1	22	13	51
L116N 46+75W	.1	4	5	12	51	22	3.54	1	20	13	86
L116N 47+00W	.1	ND	5	15	70	43	4.23	ND	34	10	68
L116N 47+25W	.1	ND	5	15	69	41	4.49	ND	34	10	75
L116N 47+50W	.1	ND	5	16	63	64	4.30	ND	29	11	78
L116N 47+75W	.1	ND	5	11	48	32	3.60	ND	26	12	86
L116N 48+00W	.1	ND	5	16	45	34	3.87	ND	30	16	97
L116N 48+25W	.1	ND	10	14	57	49	3.93	ND	30	12	82
L116N 48+50W	.1	ND	5	13	52	36	3.85	ND	27	10	69
L116N 48+75W	.1	4	ND	9	43	23	3.20	1	16	15	89
L116N 49+00W	.1	ND	30	23	47	1123	5.95	1	37	11	145
L116N 49+25W	.1	4	10	17	42	1198	4.57	ND	27	13	120
L116N 49+50W	.1	ND	5	13	52	162	3.87	ND	28	12	101
L116N 49+75W	.1	6	10	21	42	939	5.37	2	24	19	161
L116N 50+00W	.1	3	15	18	41	464	4.59	ND	27	19	120
L116N 50+25W	.1	ND	5	14	48	73	3.97	ND	29	14	135
L116N 50+50W	.1	46	25	36	22	1276	6.31	3	19	60	99
L116N 50+75W	.1	ND	25	14	45	516	4.19	ND	30	14	169
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU #PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L116N 51+00W	.1	15	ND	9	16	190	3.52	2	6	23	136
L116N 51+25W	.1	9	ND	10	41	28	3.43	1	15	12	121
L116N 51+50W	.1	11	ND	9	45	26	3.41	1	15	11	96
L116N 51+75W	.1	5	ND	13	52	75	4.36	1	21	12	98
L116N 52+00W	.1	ND	20	24	48	604	5.92	ND	37	15	108
L116N 52+25W	.1	ND	5	20	56	822	4.93	ND	45	13	121
L116N 52+50W	.1	13	30	18	37	509	4.94	5	20	58	94
L116N 52+75W	.1	ND	ND	15	42	168	4.20	ND	38	6	109
L116N 53+00W	.1	ND	ND	13	38	104	4.20	ND	29	12	162
L116N 53+25W	.1	3	ND	14	52	144	3.78	1	88	12	96
L116N 53+50W	.1	9	ND	8	30	33	2.95	1	16	13	85
L116N 53+75W	.1	25	60	31	28	695	7.84	16	49	18	209
L116N 54+00W	.1	16	40	16	33	464	4.94	6	21	17	139
L116N 54+25W	.1	ND	20	14	32	259	3.89	1	24	21	332
L116N 54+50W	.1	ND	20	20	40	151	4.84	ND	32	35	237
L116N 54+75W	.1	ND	5	13	43	69	3.81	ND	31	11	140
L116N 55+00W	.4	ND	15	15	49	177	4.63	ND	33	14	142
L116N 55+25W	.1	ND	25	17	44	449	4.51	1	34	15	130
L116N 55+50W	.1	ND	20	18	43	382	4.65	ND	38	9	93
L116N 55+75W	.1	5	10	13	27	133	4.25	1	19	14	177
L116N 56+00W	.3	ND	15	21	47	546	5.03	ND	40	16	152
L116N 56+25W	.1	ND	20	14	36	218	4.62	ND	23	16	143
L116N 56+50W	.1	ND	5	13	33	170	4.90	1	18	18	175
L116N 56+75W	.1	ND	5	23	15	379	4.68	4	13	12	301
L116N 57+25W	.1	ND	5	14	39	147	5.19	1	20	45	265
L116N 57+50W	.1	6	15	11	25	185	4.16	1	12	22	170
L116N 57+75W	.1	3	10	8	25	95	3.91	2	9	17	149
L116N 58+00W	.1	4	10	29	18	131	3.98	1	10	21	275
L118N 50+50W	.1	3	15	13	42	119	4.27	1	21	16	86
L118N 51+00W	.1	ND	10	15	54	128	4.95	1	25	18	135
L118N 51+25W	.1	ND	10	15	45	140	4.48	1	26	18	148
L118N 51+50W	.1	ND	10	18	62	345	4.80	1	36	17	120
L118N 51+75W	.1	ND	15	16	63	952	5.00	ND	38	35	109
L118N 52+00W	.1	ND	5	16	60	1031	5.03	ND	39	33	114
L118N 52+25W	.1	ND	10	17	83	109	4.88	ND	40	13	72
L118N 52+50W	.1	ND	5	16	65	53	4.56	ND	41	8	96
L118N 52+75W	.1	ND	15	21	77	113	4.94	ND	50	12	78
L118N 53+00W	.1	ND	5	12	52	30	3.61	ND	26	14	128
L118N 53+25W	.1	4	5	22	66	224	4.67	4	60	23	92
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L118N 53+50W	.1	32	15	34	65	378	6.18	8	178	50	122
L118N 53+75W	.1	ND	10	20	64	248	4.81	2	62	24	300
L118N 54+00W	.1	ND	5	16	54	126	4.61	3	32	14	78
L118N 54+25W	.1	ND	10	14	46	90	3.85	1	31	13	84
L118N 54+50W	.1	6	5	11	39	48	3.35	ND	25	12	107
L118N 54+75W	.1	ND	5	18	82	125	5.01	ND	47	13	80
L118N 55+00W	.1	ND	5	14	57	125	4.26	ND	40	12	124
L118N 55+25W	.1	5	5	15	50	157	4.23	1	29	14	114
L118N 55+50W	.1	5	35	18	57	162	4.51	1	35	16	98
L118N 55+75W	.1	5	15	16	48	124	4.10	1	26	13	100
L118N 56+00W	.1	4	15	12	43	107	4.24	1	21	12	120
L118N 56+25W	.1	ND	15	15	52	138	4.78	ND	34	16	154
L118N 56+50W	.1	ND	25	12	49	139	4.47	1	30	15	134
L118N 56+75W	.1	ND	10	11	46	157	4.29	1	28	9	157
L118N 57+00W	.1	8	5	13	34	142	4.04	1	20	22	87
L118N 57+25W	.1	ND	5	19	82	189	4.66	1	83	12	108
L120N 46+50W	.1	ND	5	19	53	65	4.58	ND	51	19	98
L120N 46+75W	.1	4	5	11	37	45	3.15	ND	31	10	84
L120N 47+00W	.1	5	5	11	37	45	3.06	1	28	13	69
L120N 47+25W	.1	9	10	7	31	29	2.45	1	19	12	57
L120N 47+50W	.1	8	ND	11	49	33	3.16	1	40	12	67
L120N 47+75W	.1	5	ND	10	43	28	2.96	ND	26	12	61
L120N 48+00W	.1	ND	ND	12	56	48	3.72	ND	36	8	73
L120N 48+25W	.1	ND	ND	13	61	51	4.02	ND	36	4	79
L120N 48+50W	.1	ND	5	14	77	43	4.29	ND	35	12	83
L120N 48+75W	.1	ND	20	12	61	47	4.42	ND	32	7	101
L120N 49+00W	.1	6	5	10	45	201	2.97	1	23	13	92
L120N 49+25W	.1	ND	5	14	67	244	4.90	ND	34	13	126
L120N 49+50W	.1	ND	5	21	68	797	4.87	ND	48	6	84
L120N 49+75W	.1	ND	5	19	72	638	4.59	ND	49	11	78
L120N 50+25W	.1	ND	5	18	61	192	4.15	ND	30	9	132
L120N 50+50W	.1	ND	5	16	63	114	4.29	ND	40	8	78
L120N 50+75W	.1	ND	5	18	74	133	4.46	ND	41	8	78
L120N 51+00W	.1	ND	5	19	68	311	4.58	1	44	12	90
L120N 51+25W	.1	ND	5	16	65	109	4.41	1	40	11	114
L120N 51+50W	.1	ND	10	19	73	148	4.92	ND	46	9	104
L120N 51+75W	.1	ND	5	16	71	108	4.58	ND	36	7	115
L120N 52+00W	.1	ND	5	13	63	58	4.31	1	29	5	72
L120N 52+50W	.1	ND	5	15	66	69	3.98	1	50	8	54
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L120N 52+75W	.1	9	5	16	66	54	3.82	1	31	9	51
L120N 53+00W	.1	4	5	13	52	50	3.43	1	32	6	122
L120N 53+50W	.1	ND	5	13	53	49	3.50	1	27	6	134
L120N 53+75W	.1	5	ND	14	60	123	3.72	1	37	9	100
L120N 54+00W	.1	3	ND	18	63	77	4.24	1	36	9	75
L120N 54+25W	.1	4	5	17	73	89	4.16	1	43	11	73
L120N 54+75W	.1	3	10	17	68	59	4.02	1	39	9	58
L120N 55+25W	.1	4	5	18	65	117	4.05	1	38	14	77
L120N 55+50W	.1	9	5	13	49	41	3.37	1	26	10	52
L120N 55+75W	.1	6	5	12	35	47	3.22	2	19	10	58
L120N 57+75W	.1	11	ND	10	45	41	3.12	2	16	12	74
L120N 58+00W	.1	11	ND	9	38	35	2.80	2	14	13	66
L122N 47+25W	.1	9	ND	13	44	85	3.07	1	22	12	56
L122N 47+50W	.1	8	ND	14	47	86	3.29	1	24	12	61
L122N 47+75W	.3	3	ND	13	61	42	3.71	1	25	10	110
L122N 48+00W	.5	4	10	13	60	34	3.60	1	30	10	102
L122N 48+25W	.3	7	10	14	53	33	3.54	1	26	11	67
L122N 48+50W	.1	5	10	12	50	26	3.32	1	30	10	85
L122N 48+75W	.1	9	ND	11	34	38	2.89	1	20	10	53
L122N 49+00W	.5	11	ND	10	41	30	2.95	1	19	12	65
L122N 49+25W	.1	9	ND	12	35	33	2.83	1	25	12	46
L122N 49+50W	.1	9	ND	10	48	31	3.04	1	24	10	63
L122N 49+75W	.3	5	5	15	63	91	3.87	2	35	13	65
L122N 50+00W	.3	ND	5	14	61	191	3.83	1	34	11	97
L122N 50+25W	.1	5	20	14	55	216	3.68	1	25	9	63
L122N 50+50W	.1	9	10	16	58	206	3.86	1	30	11	58
L122N 50+75W	.1	ND	5	13	43	187	3.58	1	31	10	70
L122N 51+00W	.1	5	5	13	42	177	3.58	1	31	10	66
L122N 51+25W	.7	3	10	15	52	346	3.43	ND	40	10	63
L122N 51+50W	.1	6	5	13	56	66	3.71	1	28	12	68
L122N 51+75W	.1	ND	ND	18	63	123	4.05	1	37	13	64
L122N 52+00W	.1	4	ND	14	54	122	3.72	1	31	11	63
L122N 52+25W	.1	ND	ND	20	71	103	4.41	ND	44	10	67
L122N 52+50W	.1	ND	ND	20	67	98	4.40	ND	41	10	111
L122N 52+75W	.1	3	ND	14	63	57	3.97	2	29	10	126
L122N 53+75W	.1	ND	ND	23	55	230	5.01	ND	46	12	142
L122N 54+00W	.1	5	ND	14	49	74	3.85	1	27	11	65
L122N 54+25W	.1	5	ND	17	72	84	4.31	1	34	12	63
L122N 54+50W	.1	ND	ND	12	49	49	3.29	ND	30	6	93
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L122N 54+75W	.1	5	ND	14	58	47	3.92	1	28	12	68
L122N 55+00W	.1	ND	ND	18	57	77	4.15	ND	54	18	119
L122N 55+25W	.1	ND	ND	18	56	76	4.07	ND	52	18	117
L122N 55+50W	.1	ND	ND	14	62	48	3.75	1	45	16	92
L122N 55+75W	.1	5	ND	16	67	92	4.45	1	42	17	92
L122N 56+00W	.1	3	ND	13	68	43	4.08	1	34	14	86
L122N 56+25W	.1	ND	ND	12	60	48	3.87	1	34	15	100
L122N 56+50W	.1	6	ND	11	58	57	3.82	2	27	15	100
L122N 56+75W	.1	11	ND	7	48	21	2.65	2	15	13	75
L122N 57+00W	.1	16	ND	6	36	14	1.92	2	10	12	58
L122N 57+25W	.1	ND	ND	15	71	55	4.25	1	44	15	82
L122N 57+50W	.1	6	ND	13	65	44	3.79	1	36	12	80
L122N 57+75W	.1	13	ND	9	43	20	2.52	2	14	13	73
L122N 58+00W	.1	6	20	12	47	70	3.67	1	27	19	112
L124N 49+00W	.1	6	20	11	46	32	3.34	1	24	11	86
L124N 49+25W	.1	9	5	11	44	31	3.16	1	23	11	84
L124N 49+50W	.1	8	5	11	46	35	3.13	1	21	10	59
L124N 49+75W	.1	4	5	15	53	45	3.79	1	25	11	66
L124N 50+00W	.1	4	5	14	53	45	3.75	1	26	12	63
L124N 50+25W	.1	8	5	11	42	45	3.04	1	26	13	51
L124N 50+50W	.1	ND	5	16	60	118	4.05	1	33	17	57
L124N 50+75W	.1	ND	10	16	59	256	4.08	ND	40	16	63
L124N 51+00W	.1	ND	5	21	70	265	4.89	ND	45	16	88
L124N 51+25W	.1	ND	10	20	68	250	4.70	ND	45	19	86
L124N 51+50W	.1	8	ND	9	36	23	2.97	1	15	7	55
L124N 51+75W	.1	8	ND	10	34	45	2.70	1	18	5	48
L124N 52+00W	.1	4	ND	11	50	45	3.44	1	20	4	62
L124N 52+25W	.1	5	ND	10	37	67	3.04	1	19	8	57
L124N 52+50W	.1	3	ND	12	44	75	3.45	1	24	7	64
L124N 52+75W	.1	ND	ND	12	41	40	3.25	1	20	3	75
L124N 53+00W	.1	ND	ND	13	46	49	3.66	ND	23	4	65
L124N 53+25W	.1	ND	ND	11	51	49	3.37	1	24	3	70
L124N 53+50W	.1	ND	ND	13	44	108	3.37	ND	24	5	51
L124N 53+75W	.1	ND	ND	16	64	168	4.26	ND	36	3	66
L124N 54+00W	.1	ND	ND	12	57	42	3.83	ND	24	7	105
L124N 55+00W	.1	ND	ND	14	66	56	4.12	ND	30	8	92
L124N 55+25W	.1	ND	ND	12	78	30	4.37	1	29	6	87
L124N 55+50W	.1	ND	10	13	31	112	3.74	ND	19	3	61
L124N 55+75W	.1	ND	10	11	43	150	3.33	ND	26	2	53
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE Z	MO PPM	NI PPM	PB PPM	ZN PPM
L124N 56+00W	.1	8	ND	9	28	83	2.91	ND	13	1	41
L124N 56+25W	.1	ND	ND	11	48	37	3.59	ND	21	4	72
L124N 56+50W	.1	5	ND	12	42	45	3.59	ND	17	7	51
L124N 56+75W	.1	ND	10	13	61	35	3.69	ND	34	5	60
L124N 57+00W	.1	ND	5	9	25	19	3.37	ND	8	8	77
L124N 57+25W	.1	ND	ND	10	13	15	3.54	ND	6	7	96
L124N 57+50W	.1	ND	15	11	45	31	3.54	ND	19	5	57
L124N 57+75W	.1	ND	ND	9	19	17	3.40	ND	13	4	79
L124N 58+00W	.1	ND	ND	10	47	26	3.47	ND	19	6	46
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

VANGEOCHEM LAB LIMITED

MAIN OFFICE: 1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604)986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -= NOT ANALYZED, *AU= AQUA REGA/AAS

COMPANY: E & B EXPLORATIONS REPORT#: 860507PA DATE RECEIVED: 86/10/03
 ATTENTION: L.SALEKEN & M.TINDALL JOB#: 860507 DATE COMPLETED: 86/10/07
 PROJECT: 5061-CB PD#5586 INVOICE#: 860507NA COPY SENT TO: VANCOUVER OFFICE

ANALYST W. Reeves

PAGE 1 OF 2

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CD PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L92N 57+25W	.1	4	25	12	23	324	2.59	2	16	1	156
L92N 57+50W	.1	7	25	11	21	111	3.20	1	14	3	105
L92N 57+75W	.1	14	5	6	15	25	2.16	1	6	7	103
L92N 58+00W	.1	5	15	11	21	97	3.33	1	12	5	122
L92N 58+25W	.1	7	15	12	20	106	3.20	1	12	6	120
L92N 58+50W	.2	7	20	17	23	217	3.66	1	18	10	76
L92N 58+75W	.1	14	25	12	22	87	3.04	1	12	5	57
L92N 59+00W	.1	11	5	8	17	38	2.31	1	7	6	64
L92N 59+25W	.3	14	20	11	22	92	3.00	1	11	6	55
L92N 59+50W	.2	11	15	12	19	82	2.72	1	10	6	82
L92N 59+75W	.2	11	30	12	19	115	3.04	1	11	8	69
L92N 60+00W	.1	ND	25	10	20	71	3.25	ND	12	8	162
L92N 60+25W	.1	ND	15	15	24	64	2.99	ND	18	7	217
L92N 60+50W	.4	ND	35	21	28	353	4.49	1	21	9	108
L92N 60+75W	.4	7	25	17	23	215	3.90	1	17	11	86
L92N 61+00W	.2	9	15	13	21	128	3.17	1	13	8	72
L92N 61+25W	.2	11	15	12	20	116	3.02	1	11	6	67
L92N 61+50W	.4	15	20	13	18	124	3.29	1	10	7	75
L92N 61+75W	.3	5	5	11	20	109	3.09	1	13	3	105
L92N 62+00W	.1	ND	5	12	25	107	2.81	1	19	ND	145
L92N 62+25W	.3	8	5	13	24	107	2.99	1	23	3	70
L92N 62+50W	.2	3	5	10	25	74	2.82	1	19	1	99
L92N 62+75W	.1	ND	5	15	31	126	3.52	ND	22	1	87
L92N 63+00W	.1	ND	20	15	37	206	3.58	ND	20	4	86
L92N 63+25W	.2	7	5	13	24	97	3.16	1	16	5	53
L98N 57+50W	.1	ND	25	10	32	1857	2.72	1	22	ND	52
L98N 57+75W	.1	ND	30	11	26	501	2.97	1	20	2	70
L98N 58+00W	.1	ND	40	15	30	490	3.02	1	26	5	77
L98N 58+25W	.3	ND	60	13	34	378	3.37	1	31	3	80
L98N 58+50W	.2	3	35	16	32	438	3.62	1	23	16	76
L98N 58+75W	.2	8	50	16	29	265	3.52	2	17	2	62
L98N 59+25W	.1	ND	40	16	25	1192	3.50	ND	22	ND	71
L98N 59+50W	.1	10	55	12	25	321	3.22	2	15	2	64
L98N 59+75W	.3	ND	110	22	39	622	4.40	8	26	12	85
L98N 60+25W	.4	ND	50	16	51	202	4.50	5	24	16	272
L98N 60+50W	.5	ND	50	16	27	475	4.15	6	18	14	123
L98N 60+75W	.6	ND	30	13	29	1130	3.90	1	20	11	109
L98N 61+00W	.3	5	50	20	25	1361	4.37	2	17	9	94
L98N 61+25W	.3	ND	50	21	26	1032	4.58	2	21	11	111
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L98N 61+50W	.1	ND	50	18	25	851	4.29	1	20	14	103
L98N 61+75W	.1	ND	70	17	36	825	4.19	2	19	14	107
L98N 62+25W	.1	ND	75	16	21	1452	4.22	3	14	15	92
L98N 62+50W	.5	ND	55	26	24	1933	5.29	6	17	4	95
L98N 62+75W	.2	ND	70	21	23	2570	4.74	5	16	10	100
L98N 63+00W	.2	ND	80	20	21	1321	4.57	3	17	10	81
L98N 63+25W	.1	4	70	19	40	1190	4.40	7	18	14	99
L98N 63+50W	.3	9	55	17	24	361	4.25	1	13	21	74
L98N 63+75W	.4	3	30	16	25	538	4.07	1	13	15	131
L98N 64+00W	.3	6	15	10	20	108	3.25	ND	9	13	125
L98N 64+25W	1.1	ND	15	21	40	1519	4.45	4	33	12	195
L98N 64+50W	.3	ND	25	17	31	361	3.90	6	17	11	132
L98N 65+00W	.3	ND	55	19	29	261	3.95	3	14	10	175
L98N 65+25W	.2	11	35	12	23	158	3.45	1	14	11	110
L98N 65+50W	.2	5	10	12	39	126	3.33	2	7	14	136
L98N 65+75W	.6	ND	15	19	39	714	4.29	3	31	5	218
L98N 66+00W	.1	ND	20	13	33	100	4.04	ND	12	13	329
L98N 66+50W	.2	10	20	10	36	78	2.81	ND	11	9	63
L98N 66+75W	.4	10	25	11	19	88	3.11	ND	11	11	51
L98N 67+00W	.1	10	10	9	17	39	2.54	ND	8	7	94
L98N 67+25W	.4	5	10	10	18	52	2.77	ND	17	11	71
L98N 67+75W	.3	6	15	11	18	66	2.97	ND	13	9	130
L98N 68+00W	.2	7	15	9	16	46	2.65	ND	11	9	129
L98N 68+25W	.2	4	15	11	18	75	3.07	ND	12	9	117
L98N 68+50W	.2	10	10	10	16	35	2.63	ND	8	9	156
L98N 68+75W	.3	13	10	8	15	65	2.29	ND	8	9	33
L100N 50+25W	.1	ND	15	13	32	95	3.45	ND	34	5	63
L100N 50+50W	.1	ND	35	12	28	287	3.82	ND	22	8	78
L100N 50+75W	.1	ND	65	14	26	519	4.01	ND	22	8	97
L100N 51+00W	.1	ND	20	7	22	123	3.11	ND	15	4	77
L100N 51+25W	.1	ND	15	20	20	929	2.74	3	13	3	74
L100N 51+50W	.1	ND	15	13	24	192	3.27	ND	21	6	79
L100N 51+75W	.1	8	10	5	19	178	2.31	4	11	8	60
L100N 52+00W	.1	ND	25	12	27	284	3.27	1	19	6	60
L100N 52+25W	.1	8	20	10	21	397	2.79	2	12	6	49
L100N 52+50W	.1	ND	25	14	35	2605	3.80	12	32	2	60
L100N 52+75W	.1	ND	10	10	25	169	3.29	ND	21	8	77
L100N 53+00W	.1	ND	10	8	26	79	2.93	ND	15	7	66
L100N 53+25W	.1	ND	20	10	25	101	3.25	ND	20	6	87
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

VANGEOCHEM LAB LIMITED

M. IN OFFICE: 1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604)986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -- NOT ANALYZED, +AU= AQUA REGA/AAS

COMPANY: E & B EXPLORATIONS REPORT#: 860510PA DATE RECEIVED: 86/10/06
 ATTENTION: L. SALEKEN & M. TINDALL JOB#: 860510 DATE COMPLETED: 86/10/09
 PROJECT: 5061-CB PO#5586 INVOICE#: 860510NA COPY SENT TO: VANCOUVER OFFICE

ANALYST W. Peavey

PAGE 1 OF 4

SAMPLE NAME	AG PPM	AS PPM	AU +PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L100N 53+50W	.1	ND	10	14	36	311	3.79	1	28	9	69
L100N 53+75W	.1	9	10	10	32	430	3.53	3	24	11	74
L100N 54+00W	.3	11	5	10	33	219	3.57	3	25	13	78
L100N 54+25W	.2	8	10	12	34	333	3.32	1	23	11	63
L100N 54+50W	.3	4	20	13	37	260	3.53	1	25	14	67
L100N 54+75W	.4	15	20	10	32	163	3.11	2	17	14	54
L100N 55+00W	.3	10	20	13	33	448	3.50	2	22	14	58
L100N 55+25W	.5	ND	20	12	32	284	3.84	1	27	14	84
L100N 55+50W	.6	6	40	12	32	1244	3.70	3	21	13	61
L100N 55+75W	.5	ND	95	19	31	918	6.64	1	25	11	89
L100N 56+00W	1.2	5	400	12	18	567	5.57	2	12	21	78
L100N 56+50W	1.2	4	525	17	20	1332	6.14	2	13	20	70
L100N 56+75W	.6	17	70	8	22	288	2.85	2	13	15	61
L100N 57+00W	.2	11	20	11	28	124	3.01	1	17	13	69
L100N 57+25W	.4	8	20	12	29	163	3.60	1	20	12	99
L100N 58+00W	.6	ND	60	12	31	283	3.89	1	21	17	138
L100N 58+25W	.8	ND	75	15	30	653	4.57	1	23	19	132
L100N 58+50W	1.1	ND	25	14	47	691	3.95	1	44	17	124
L100N 58+75W	.5	ND	55	21	11	2271	5.89	ND	11	8	166
L100N 59+00W	.6	ND	40	16	64	517	3.66	1	63	14	131
L100N 59+25W	1.1	8	10	12	34	198	3.27	1	24	13	83
L100N 59+50W	.3	ND	20	16	51	1013	3.62	ND	36	6	70
L100N 59+75W	.4	ND	35	11	38	300	3.33	2	33	12	64
L100N 60+00W	1.1	ND	360	19	17	1623	6.07	ND	12	9	69
L100N 60+25W	.6	ND	85	18	31	1413	4.34	1	26	5	116
L100N 60+50W	.1	ND	10	12	44	168	3.04	1	37	28	97
L100N 60+75W	.8	ND	150	15	13	666	3.91	ND	12	9	103
L100N 61+00W	.6	ND	90	17	19	1159	4.31	5	17	4	58
L100N 61+25W	.6	ND	90	18	19	1231	4.50	7	18	1	54
L100N 61+50W	.8	4	30	10	16	508	3.57	3	15	9	115
L100N 61+75W	.5	ND	10	16	34	283	2.71	2	28	9	181
L100N 62+00W	.3	ND	65	11	26	326	4.18	2	19	7	163
L100N 62+25W	.4	3	85	11	23	148	3.50	2	13	9	150
L100N 62+50W	.3	ND	50	15	37	174	3.67	3	17	10	215
L100N 62+75W	.6	ND	65	13	30	568	4.14	2	16	14	189
L100N 63+25W	.3	6	5	12	11	123	3.64	2	9	20	130
L100N 63+50W	.2	ND	20	14	14	307	3.70	1	10	12	235
L100N 63+75W	.1	ND	25	17	24	354	4.29	2	16	14	194
L100N 64+00W	.1	8	5	14	20	143	3.27	2	10	12	196
DETECTION LIMIT	.1	3	+5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L100N 64+25W	ND	ND	20	12	20	197	3.44	1	11	12	133
L100N 64+50W	.4	3	15	12	21	155	3.21	1	11	10	241
L100N 64+75W	.3	3	5	11	20	71	2.88	2	10	13	183
L100N 65+00W	.1	ND	30	17	32	404	4.26	3	20	9	103
L100N 65+25W	.1	ND	40	19	31	403	4.36	3	21	8	99
L100N 65+50W	.2	ND	20	15	25	237	3.63	2	14	9	124
L100N 66+25W	.4	3	5	13	19	97	3.21	2	10	16	241
L100N 66+50W	.2	4	15	14	20	174	3.86	1	15	12	83
L100N 66+75W	.3	7	5	7	16	41	2.52	1	6	14	85
L100N 67+00W	.1	5	30	10	18	38	3.06	1	8	11	129
L100N 67+25W	.3	5	15	11	19	58	2.99	1	13	10	139
L100N 67+50W	.4	7	25	10	17	44	3.12	1	9	14	106
L100N 67+75W	.4	9	15	9	18	34	2.73	1	7	11	121
L100N 68+00W	.4	14	10	8	15	31	2.63	1	4	15	84
L100N 68+25W	.5	ND	5	13	24	31	3.60	ND	10	14	219
L100N 68+50W	.3	6	35	11	18	113	3.62	1	13	12	105
L100N 68+75W	.3	5	15	10	24	93	3.30	1	10	13	84
L100N 69+00W	.1	12	10	10	19	103	2.65	1	12	10	78
L100N 69+25W	.2	ND	25	16	25	79	3.92	1	11	11	194
L100N 69+50W	.3	4	5	11	21	79	3.61	1	12	11	70
L102N 50+25W	ND	ND	5	11	33	38	3.39	ND	34	13	117
L102N 50+50W	ND	ND	5	10	31	27	3.16	1	23	15	119
L102N 50+75W	.3	ND	5	12	32	85	3.22	1	22	10	208
L102N 51+00W	ND	ND	15	14	38	90	3.95	ND	34	7	125
L102N 51+25W	ND	ND	5	13	48	127	4.32	ND	35	8	131
L102N 51+50W	.1	ND	5	12	30	141	3.41	ND	24	10	154
L102N 51+75W	.1	ND	5	14	47	82	3.79	ND	38	9	61
L102N 52+00W	.6	ND	30	11	32	98	3.66	ND	24	12	107
L102N 52+25W	.2	ND	5	17	32	138	3.82	ND	27	10	116
L102N 52+50W	.4	ND	5	14	29	94	3.44	ND	22	10	109
L102N 52+75W	ND	ND	5	17	40	147	3.97	ND	33	8	78
L102N 53+00W	ND	ND	10	16	40	137	4.14	ND	34	8	98
L102N 53+25W	.2	ND	10	11	32	68	3.76	1	18	10	109
L102N 53+50W	.2	ND	5	7	24	36	2.85	1	12	12	94
L102N 53+75W	.2	ND	75	15	24	378	5.69	12	13	78	199
L102N 54+00W	ND	ND	30	16	26	190	5.00	5	21	9	256
L102N 54+75W	.1	ND	160	11	26	1079	4.87	2	19	5	110
L102N 55+00W	.1	ND	110	10	27	390	4.17	1	15	7	85
L102N 55+25W	ND	ND	20	14	36	484	3.89	ND	26	6	69
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L102N 55+50W	.1	5	5	9	28	206	3.57	1	19	8	72
L102N 55+75W	.1	ND	10	15	41	680	4.19	ND	34	11	77
L102N 56+00W	.1	ND	50	11	35	711	4.37	1	24	11	78
L102N 56+25W	.1	ND	65	17	39	2550	4.41	ND	35	9	68
L102N 56+50W	.1	ND	60	13	36	1160	4.32	1	29	9	75
L102N 56+75W	.1	3	130	13	31	901	3.84	1	30	5	48
L102N 57+00W	.1	ND	25	12	35	332	4.00	ND	28	6	79
L102N 57+25W	.1	ND	25	13	32	233	3.49	1	25	8	83
L102N 57+50W	.1	ND	10	13	35	236	3.72	1	27	10	90
L102N 57+75W	.1	6	30	15	39	339	3.75	1	31	7	55
L102N 58+00W	.1	10	10	11	31	191	3.20	1	21	9	69
L102N 58+25W	.3	3	80	24	26	1232	5.29	4	30	16	124
L102N 58+50W	.4	ND	55	20	28	734	4.60	2	23	14	92
L102N 58+75W	.1	ND	30	12	28	149	3.45	1	18	10	81
L102N 59+00W	.1	3	30	12	27	149	3.40	1	18	11	78
L102N 59+25W	.1	ND	30	13	27	191	3.45	1	20	9	91
L102N 59+50W	.1	7	15	12	29	170	3.13	2	23	15	62
L102N 59+75W	.1	ND	50	18	35	306	4.22	ND	39	9	72
L102N 60+00W	.2	ND	25	16	24	219	3.87	ND	23	11	72
L102N 60+25W	.1	ND	90	14	31	629	4.44	ND	32	10	123
L102N 60+50W	.1	ND	55	11	32	225	3.52	1	28	10	60
L102N 60+75W	.3	ND	40	17	28	555	4.92	ND	27	11	118
L102N 61+00W	.1	ND	40	12	31	796	5.19	ND	27	10	80
L102N 61+25W	.1	ND	45	13	26	555	4.58	ND	24	8	97
L102N 61+50W	.1	ND	55	14	30	651	4.19	ND	25	8	74
L102N 61+75W	.5	ND	95	18	25	1020	5.12	1	20	8	80
L102N 62+00W	.4	ND	85	14	29	696	4.42	1	22	9	60
L102N 62+25W	.3	ND	160	13	27	694	4.32	1	19	6	62
L102N 62+50W	.4	ND	25	12	28	602	4.24	2	21	12	122
L102N 62+75W	.8	ND	240	19	12	2488	7.01	ND	18	5	245
L102N 63+00W	.5	ND	135	15	22	1060	4.60	1	18	9	133
L102N 63+25W	.3	5	85	13	23	693	4.04	2	17	6	86
L102N 63+50W	.5	11	135	12	19	612	4.25	2	14	7	69
L102N 63+75W	.4	4	50	13	17	341	3.75	2	12	7	191
L102N 64+00W	.4	10	70	11	20	375	3.60	2	13	8	138
L102N 64+50W	1.1	6	35	13	18	249	3.59	2	14	9	244
L102N 64+75W	.3	ND	55	14	24	651	4.30	2	23	11	220
L102N 65+00W	.2	ND	365	12	21	551	4.67	2	16	10	120
L102N 65+25W	.6	16	35	8	14	351	2.58	3	7	9	113
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L102N 65+50W	ND	5	45	9	15	113	2.63	1	7	9	129
L102N 65+75W	ND	ND	40	11	19	97	3.40	1	9	9	173
L102N 66+00W	.1	4	40	12	16	329	2.88	1	8	8	128
L102N 66+50W	ND	6	15	11	17	462	2.84	1	9	9	91
L102N 66+75W	.3	11	15	11	17	396	2.78	1	7	10	95
L102N 67+00W	.2	ND	40	13	24	122	3.77	1	12	12	244
L102N 67+25W	1.4	6	10	11	17	104	2.90	1	9	16	143
L102N 67+75W	.4	6	10	10	16	76	2.76	1	8	12	159
L102N 68+00W	.3	ND	5	10	8	36	3.30	1	4	9	115
L102N 68+25W	.6	5	20	10	11	56	2.66	1	7	10	162
L102N 68+50W	.3	ND	15	15	18	61	2.27	2	12	30	233
L102N 68+75W	.4	ND	15	14	23	146	3.25	1	16	15	179
L102N 69+00W	.3	ND	10	13	21	471	3.47	ND	15	13	166
L102N 69+25W	.2	ND	20	14	22	515	3.62	ND	14	12	173
L102N 69+50W	.1	ND	10	13	22	266	3.50	1	18	5	189
L102N 69+75W	.4	4	10	14	21	121	3.59	1	10	11	161
L102N 70+00W	.2	11	35	13	21	167	3.15	1	14	11	85
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

VANGEOCHEM LAB LIMITED

MAIN OFFICE: 1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604) 986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604) 251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND
 IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -= NOT ANALYZED, *AU= AQUA REGIA/AAS

COMPANY: E & B EXPLORATIONS REPORT#: 860510PA DATE RECEIVED: 86/10/06
 ATTENTION: L.SALEKEN & M.TINDALL JOB#: 860510 DATE COMPLETED: 86/10/09
 PROJECT: 5061-CB P0#5586 INVOICE#: 860510NA COPY SENT TO: VANCOUVER OFFICE

ANALYST W. P. Pains

PAGE 1 OF 4

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L100N 53+50W	.1	ND	10	14	36	311	3.79	1	28	9	69
L100N 53+75W	.1	9	10	10	32	430	3.53	3	24	11	74
L100N 54+00W	.3	11	5	10	33	219	3.57	3	25	13	78
L100N 54+25W	.2	8	10	12	34	333	3.32	1	23	11	63
L100N 54+50W	.3	4	20	13	37	260	3.53	1	25	14	67
L100N 54+75W	.4	15	20	10	32	163	3.11	2	17	14	54
L100N 55+00W	.3	10	20	13	33	448	3.50	2	22	14	58
L100N 55+25W	.5	ND	20	12	32	284	3.84	1	27	14	84
L100N 55+50W	.6	6	40	12	32	1244	3.70	3	21	13	61
L100N 55+75W	.5	ND	95	19	31	918	6.64	1	25	11	89
L100N 56+00W	1.2	5	400	12	18	567	5.57	2	12	21	78
L100N 56+50W	1.2	4	525	17	20	1332	6.14	2	13	20	70
L100N 56+75W	.6	17	70	8	22	288	2.85	2	13	15	61
L100N 57+00W	.2	11	20	11	28	124	3.01	1	17	13	69
L100N 57+25W	.4	8	20	12	29	163	3.60	1	20	12	99
L100N 58+00W	.6	ND	60	12	31	283	3.89	1	21	17	138
L100N 58+25W	.8	ND	75	15	30	653	4.57	1	23	19	132
L100N 58+50W	1.1	ND	25	14	47	691	3.95	1	44	17	124
L100N 58+75W	.5	ND	55	21	11	2271	5.89	ND	11	8	166
L100N 59+00W	.6	ND	40	16	64	517	3.66	1	63	14	131
L100N 59+25W	1.1	8	10	12	34	198	3.27	1	24	13	83
L100N 59+50W	.3	ND	20	16	51	1013	3.62	ND	36	6	70
L100N 59+75W	.4	ND	35	11	38	300	3.33	2	33	12	64
L100N 60+00W	1.1	ND	360	19	17	1623	6.07	ND	12	9	69
L100N 60+25W	.6	ND	85	18	31	1413	4.34	1	26	5	116
L100N 60+50W	.1	ND	10	12	44	168	3.04	1	37	28	97
L100N 60+75W	.8	ND	150	15	13	666	3.91	ND	12	9	103
L100N 61+00W	.6	ND	90	17	19	1159	4.31	5	17	4	58
L100N 61+25W	.6	ND	90	18	19	1231	4.50	7	18	1	54
L100N 61+50W	.8	4	30	10	16	508	3.57	3	15	9	115
L100N 61+75W	.5	ND	10	16	34	283	2.71	2	28	9	181
L100N 62+00W	.3	ND	65	11	26	326	4.18	2	19	7	163
L100N 62+25W	.4	3	85	11	23	148	3.50	2	13	9	150
L100N 62+50W	.3	ND	50	15	37	174	3.67	3	17	10	215
L100N 62+75W	.6	ND	65	13	30	568	4.14	2	16	14	189
L100N 63+25W	.3	6	5	12	11	123	3.64	2	9	20	130
L100N 63+50W	.2	ND	20	14	14	307	3.70	1	10	12	235
L100N 63+75W	.1	ND	25	17	24	354	4.29	2	16	14	194
L100N 64+00W	.1	8	5	14	20	143	3.27	2	10	12	196
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L100N 64+25W	ND	ND	20	12	20	197	3.44	1	11	12	133
L100N 64+50W	.4	3	15	12	21	155	3.21	1	11	10	241
L100N 64+75W	.3	3	5	11	20	71	2.88	2	10	13	183
L100N 65+00W	.1	ND	30	17	32	404	4.26	3	20	9	103
L100N 65+25W	.1	ND	40	19	31	403	4.36	3	21	8	99
L100N 65+50W	.2	ND	20	15	25	237	3.63	2	14	9	124
L100N 66+25W	.4	3	5	13	19	97	3.21	2	10	16	241
L100N 66+50W	.2	4	15	14	20	174	3.86	1	15	12	83
L100N 66+75W	.3	7	5	7	16	41	2.52	1	6	14	85
L100N 67+00W	.1	5	30	10	18	38	3.06	1	8	11	129
L100N 67+25W	.3	5	15	11	19	58	2.99	1	13	10	139
L100N 67+50W	.4	7	25	10	17	44	3.12	1	9	14	106
L100N 67+75W	.4	9	15	9	18	34	2.73	1	7	11	121
L100N 68+00W	.4	14	10	8	15	31	2.63	1	4	15	84
L100N 68+25W	.5	ND	5	13	24	31	3.60	ND	10	14	219
L100N 68+50W	.3	6	35	11	18	113	3.62	1	13	12	105
L100N 68+75W	.3	5	15	10	24	93	3.30	1	10	13	84
L100N 69+00W	.1	12	10	10	19	103	2.65	1	12	10	78
L100N 69+25W	.2	ND	25	16	25	79	3.92	1	11	11	194
L100N 69+50W	.3	4	5	11	21	79	3.61	1	12	11	70
L102N 50+25W	ND	ND	5	11	33	38	3.39	ND	34	13	117
L102N 50+50W	ND	ND	5	10	31	27	3.16	1	23	15	119
L102N 50+75W	.3	ND	5	12	32	85	3.22	1	22	10	208
L102N 51+00W	ND	ND	15	14	38	90	3.95	ND	34	7	125
L102N 51+25W	ND	ND	5	13	48	127	4.32	ND	35	8	131
L102N 51+50W	.1	ND	5	12	30	141	3.41	ND	24	10	154
L102N 51+75W	.1	ND	5	14	47	82	3.79	ND	38	9	61
L102N 52+00W	.6	ND	30	11	32	98	3.66	ND	24	12	107
L102N 52+25W	.2	ND	5	17	32	138	3.82	ND	27	10	116
L102N 52+50W	.4	ND	5	14	29	94	3.44	ND	22	10	109
L102N 52+75W	ND	ND	5	17	40	147	3.97	ND	33	8	78
L102N 53+00W	ND	ND	10	16	40	137	4.14	ND	34	8	98
L102N 53+25W	.2	ND	10	11	32	68	3.76	1	18	10	109
L102N 53+50W	.2	ND	5	7	24	36	2.85	1	12	12	94
L102N 53+75W	.2	ND	75	15	24	378	5.69	12	13	78	199
L102N 54+00W	ND	ND	30	16	26	190	5.00	5	21	9	256
L102N 54+75W	.1	ND	160	11	26	1079	4.87	2	19	5	110
L102N 55+00W	.1	ND	110	10	27	390	4.17	1	15	7	85
L102N 55+25W	ND	ND	20	14	36	484	3.89	ND	26	6	69
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L102N 55+50W	.1	5	5	9	28	206	3.57	1	19	8	72
L102N 55+75W	.1	ND	10	15	41	680	4.19	ND	34	11	77
L102N 56+00W	.1	ND	50	11	35	711	4.37	1	24	11	78
L102N 56+25W	.1	ND	65	17	39	2550	4.41	ND	35	9	68
L102N 56+50W	.1	ND	60	13	36	1160	4.32	1	29	9	75
L102N 56+75W	.1	3	130	13	31	901	3.84	1	30	5	48
L102N 57+00W	.1	ND	25	12	35	332	4.00	ND	28	6	79
L102N 57+25W	.1	ND	25	13	32	233	3.49	1	25	8	83
L102N 57+50W	.1	ND	10	13	35	236	3.72	1	27	10	90
L102N 57+75W	.1	6	30	15	39	339	3.75	1	31	7	55
L102N 58+00W	.1	10	10	11	31	191	3.20	1	21	9	69
L102N 58+25W	.3	3	80	24	26	1232	5.29	4	30	16	124
L102N 58+50W	.4	ND	55	20	28	734	4.60	2	23	14	92
L102N 58+75W	.1	ND	30	12	28	149	3.45	1	18	10	81
L102N 59+00W	.1	3	30	12	27	149	3.40	1	18	11	78
L102N 59+25W	.1	ND	30	13	27	191	3.45	1	20	9	91
L102N 59+50W	.1	7	15	12	29	170	3.13	2	23	15	62
L102N 59+75W	.1	ND	50	18	35	306	4.22	ND	39	9	72
L102N 60+00W	.2	ND	25	16	24	219	3.87	ND	23	11	72
L102N 60+25W	.1	ND	90	14	31	629	4.44	ND	32	10	123
L102N 60+50W	.1	ND	55	11	32	225	3.52	1	28	10	60
L102N 60+75W	.3	ND	40	17	28	555	4.92	ND	27	11	118
L102N 61+00W	.1	ND	40	12	31	796	5.19	ND	27	10	80
L102N 61+25W	.1	ND	45	13	26	555	4.58	ND	24	8	97
L102N 61+50W	.1	ND	55	14	30	651	4.19	ND	25	8	74
L102N 61+75W	.5	ND	95	18	25	1020	5.12	1	20	8	80
L102N 62+00W	.4	ND	85	14	29	696	4.42	1	22	9	60
L102N 62+25W	.3	ND	160	13	27	694	4.32	1	19	6	62
L102N 62+50W	.4	ND	25	12	28	602	4.24	2	21	12	122
L102N 62+75W	.8	ND	240	19	12	2488	7.01	ND	18	5	245
L102N 63+00W	.5	ND	135	15	22	1060	4.60	1	18	9	133
L102N 63+25W	.3	5	85	13	23	693	4.04	2	17	6	86
L102N 63+50W	.5	11	135	12	19	612	4.25	2	14	7	69
L102N 63+75W	.4	4	50	13	17	341	3.75	2	12	7	191
L102N 64+00W	.4	10	70	11	20	375	3.60	2	13	8	138
L102N 64+50W	1.1	6	35	13	18	249	3.59	2	14	9	244
L102N 64+75W	.3	ND	55	14	24	651	4.30	2	23	11	220
L102N 65+00W	.2	ND	365	12	21	551	4.67	2	16	10	120
L102N 65+25W	.6	16	35	8	14	351	2.58	3	7	9	113
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L102N 65+50W	ND	5	45	9	15	113	2.63	1	7	9	129
L102N 65+75W	ND	ND	40	11	19	97	3.40	1	9	9	173
L102N 66+00W	.1	4	40	12	16	329	2.88	1	8	8	128
L102N 66+50W	ND	6	15	11	17	462	2.84	1	9	9	91
L102N 66+75W	.3	11	15	11	17	396	2.78	1	7	10	95
L102N 67+00W	.2	ND	40	13	24	122	3.77	1	12	12	244
L102N 67+25W	1.4	6	10	11	17	104	2.90	1	9	16	143
L102N 67+75W	.4	6	10	10	16	76	2.76	1	8	12	159
L102N 68+00W	.3	ND	5	10	8	36	3.30	1	4	9	115
L102N 68+25W	.6	5	20	10	11	56	2.66	1	7	10	162
L102N 68+50W	.3	ND	15	15	18	61	2.27	2	12	30	233
L102N 68+75W	.4	ND	15	14	23	146	3.25	1	16	15	179
L102N 69+00W	.3	ND	10	13	21	471	3.47	ND	15	13	166
L102N 69+25W	.2	ND	20	14	22	515	3.62	ND	14	12	173
L102N 69+50W	.1	ND	10	13	22	266	3.50	1	18	5	189
L102N 69+75W	.4	4	10	14	21	121	3.59	1	10	11	161
L102N 70+00W	.2	11	35	13	21	167	3.15	1	14	11	85
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

VANGEOCHEM LAB LIMITED

MAIN OFFICE: 1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604)986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND
 IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -= NOT ANALYZED, *AU= AQUA REGA/AAS

COMPANY: E & B EXPLORATIONS REPORT#: 860507PA DATE RECEIVED: 86/10/03
 ATTENTION: L.SALEKEN & M.TINDALL JOB#: 860507 DATE COMPLETED: 86/10/07
 PROJECT: 5061-CB PD#5586 INVOICE#: 860507NA COPY SENT TO: VANCOUVER OFFICE

ANALYST W. Reeves

PAGE 1 OF 2

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L92N 57+25W	.1	4	25	12	23	324	2.59	2	16	1	156
L92N 57+50W	.1	7	25	11	21	111	3.20	1	14	3	105
L92N 57+75W	.1	14	5	6	15	25	2.16	1	6	7	103
L92N 58+00W	.1	5	15	11	21	97	3.33	1	12	5	122
L92N 58+25W	.1	7	15	12	20	106	3.20	1	12	6	120
L92N 58+50W	.2	7	20	17	23	217	3.66	1	18	10	76
L92N 58+75W	.1	14	25	12	22	87	3.04	1	12	5	57
L92N 59+00W	.1	11	5	8	17	38	2.31	1	7	6	64
L92N 59+25W	.3	14	20	11	22	92	3.00	1	11	6	55
L92N 59+50W	.2	11	15	12	19	82	2.72	1	10	6	82
L92N 59+75W	.2	11	30	12	19	115	3.04	1	11	8	69
L92N 60+00W	.1	ND	25	10	20	71	3.25	ND	12	8	162
L92N 60+25W	.1	ND	15	15	24	64	2.99	ND	18	7	217
L92N 60+50W	.4	ND	35	21	28	353	4.49	1	21	9	108
L92N 60+75W	.4	7	25	17	23	215	3.90	1	17	11	86
L92N 61+00W	.2	9	15	13	21	128	3.17	1	13	8	72
L92N 61+25W	.2	11	15	12	20	116	3.02	1	11	6	67
L92N 61+50W	.4	15	20	13	18	124	3.29	1	10	7	75
L92N 61+75W	.3	5	5	11	20	109	3.09	1	13	3	105
L92N 62+00W	.1	ND	5	12	25	107	2.81	1	19	ND	145
L92N 62+25W	.3	8	5	13	24	107	2.99	1	23	3	70
L92N 62+50W	.2	3	5	10	25	74	2.82	1	19	1	99
L92N 62+75W	.1	ND	5	15	31	126	3.52	ND	22	1	87
L92N 63+00W	.1	ND	20	15	37	206	3.58	ND	20	4	86
L92N 63+25W	.2	7	5	13	24	97	3.16	1	16	5	53
L98N 57+50W	.1	ND	25	10	32	1857	2.72	1	22	ND	52
L98N 57+75W	.1	ND	30	11	26	501	2.97	1	20	2	70
L98N 58+00W	.1	ND	40	15	30	490	3.02	1	26	5	77
L98N 58+25W	.3	ND	60	13	34	378	3.37	1	31	3	80
L98N 58+50W	.2	3	35	16	32	438	3.62	1	23	16	76
L98N 58+75W	.2	8	50	16	29	265	3.52	2	17	2	62
L98N 59+25W	.1	ND	40	16	25	1192	3.50	ND	22	ND	71
L98N 59+50W	.1	10	55	12	25	321	3.22	2	15	2	64
L98N 59+75W	.3	ND	110	22	39	622	4.40	8	26	12	85
L98N 60+25W	.4	ND	50	16	51	202	4.50	5	24	16	272
L98N 60+50W	.5	ND	50	16	27	475	4.15	6	18	14	123
L98N 60+75W	.6	ND	30	13	29	1130	3.90	1	20	11	109
L98N 61+00W	.3	5	50	20	25	1361	4.37	2	17	9	94
L98N 61+25W	.3	ND	50	21	26	1032	4.58	2	21	11	111
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU #PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L98N 61+50W	.1	ND	50	18	25	851	4.29	1	20	14	103
L98N 61+75W	.1	ND	70	17	36	825	4.19	2	19	14	107
L98N 62+25W	.1	ND	75	16	21	1452	4.22	3	14	15	92
L98N 62+50W	.5	ND	55	26	24	1933	5.29	6	17	4	95
L98N 62+75W	.2	ND	70	21	23	2570	4.74	5	16	10	100
L98N 63+00W	.2	ND	80	20	21	1321	4.57	3	17	10	81
L98N 63+25W	.1	4	70	19	40	1190	4.40	7	18	14	99
L98N 63+50W	.3	9	55	17	24	361	4.25	1	13	21	74
L98N 63+75W	.4	3	30	16	25	538	4.07	1	13	15	131
L98N 64+00W	.3	6	15	10	20	108	3.25	ND	9	13	125
L98N 64+25W	1.1	ND	15	21	40	1519	4.45	4	33	12	195
L98N 64+50W	.3	ND	25	17	31	361	3.90	6	17	11	132
L98N 65+00W	.3	ND	55	19	29	261	3.95	3	14	10	175
L98N 65+25W	.2	11	35	12	23	158	3.45	1	14	11	110
L98N 65+50W	.2	5	10	12	39	126	3.33	2	7	14	136
L98N 65+75W	.6	ND	15	19	39	714	4.29	3	31	5	218
L98N 66+00W	.1	ND	20	13	33	100	4.04	ND	12	13	329
L98N 66+50W	.2	10	20	10	36	78	2.81	ND	11	9	63
L98N 66+75W	.4	10	25	11	19	88	3.11	ND	11	11	51
L98N 67+00W	.1	10	10	9	17	39	2.54	ND	8	7	94
L98N 67+25W	.4	5	10	10	18	52	2.77	ND	17	11	71
L98N 67+75W	.3	6	15	11	18	66	2.97	ND	13	9	130
L98N 68+00W	.2	7	15	9	16	46	2.65	ND	11	9	129
L98N 68+25W	.2	4	15	11	18	75	3.07	ND	12	9	117
L98N 68+50W	.2	10	10	10	16	35	2.63	ND	8	9	156
L98N 68+75W	.3	13	10	8	15	65	2.29	ND	8	9	33
L100N 50+25W	.1	ND	15	13	32	95	3.45	ND	34	5	63
L100N 50+50W	.1	ND	35	12	28	287	3.82	ND	22	8	78
L100N 50+75W	.1	ND	65	14	26	519	4.01	ND	22	8	97
L100N 51+00W	.1	ND	20	7	22	123	3.11	ND	15	4	77
L100N 51+25W	.1	ND	15	20	20	929	2.74	3	13	3	74
L100N 51+50W	.1	ND	15	13	24	192	3.27	ND	21	6	79
L100N 51+75W	.1	8	10	5	19	178	2.31	4	11	8	60
L100N 52+00W	.1	ND	25	12	27	284	3.27	1	19	6	60
L100N 52+25W	.1	8	20	10	21	397	2.79	2	12	6	49
L100N 52+50W	.1	ND	25	14	35	2605	3.80	12	32	2	60
L100N 52+75W	.1	ND	10	10	25	169	3.29	ND	21	8	77
L100N 53+00W	.1	ND	10	8	26	79	2.93	ND	15	7	66
L100N 53+25W	.1	ND	20	10	25	101	3.25	ND	20	6	87
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L116N 51+00W	.1	15	ND	9	16	190	3.52	2	6	23	136
L116N 51+25W	.1	9	ND	10	41	28	3.43	1	15	12	121
L116N 51+50W	.1	11	ND	9	45	26	3.41	1	15	11	96
L116N 51+75W	.1	5	ND	13	52	75	4.36	1	21	12	98
L116N 52+00W	.1	ND	20	24	48	604	5.92	ND	37	15	108
L116N 52+25W	.1	ND	5	20	56	822	4.93	ND	45	13	121
L116N 52+50W	.1	13	30	18	37	509	4.94	5	20	58	94
L116N 52+75W	.1	ND	ND	15	42	168	4.20	ND	38	6	109
L116N 53+00W	.1	ND	ND	13	38	104	4.20	ND	29	12	162
L116N 53+25W	.1	3	ND	14	52	144	3.78	1	88	12	96
L116N 53+50W	.1	9	ND	8	30	33	2.95	1	16	13	85
L116N 53+75W	.1	25	60	31	28	695	7.84	16	49	18	209
L116N 54+00W	.1	16	40	16	33	464	4.94	6	21	17	139
L116N 54+25W	.1	ND	20	14	32	259	3.89	1	24	21	332
L116N 54+50W	.1	ND	20	20	40	151	4.84	ND	32	35	237
L116N 54+75W	.1	ND	5	13	43	69	3.81	ND	31	11	140
L116N 55+00W	.4	ND	15	15	49	177	4.63	ND	33	14	142
L116N 55+25W	.1	ND	25	17	44	449	4.51	1	34	15	130
L116N 55+50W	.1	ND	20	18	43	382	4.65	ND	38	9	93
L116N 55+75W	.1	5	10	13	27	133	4.25	1	19	14	177
L116N 56+00W	.3	ND	15	21	47	546	5.03	ND	40	16	152
L116N 56+25W	.1	ND	20	14	36	218	4.62	ND	23	16	143
L116N 56+50W	.1	ND	5	13	33	170	4.90	1	18	18	175
L116N 56+75W	.1	ND	5	23	15	379	4.68	4	13	12	301
L116N 57+25W	.1	ND	5	14	39	147	5.19	1	20	45	265
L116N 57+50W	.1	6	15	11	25	185	4.16	1	12	22	170
L116N 57+75W	.1	3	10	8	25	95	3.91	2	9	17	149
L116N 58+00W	.1	4	10	29	18	131	3.98	1	10	21	275
L118N 50+50W	.1	3	15	13	42	119	4.27	1	21	16	86
L118N 51+00W	.1	ND	10	15	54	128	4.95	1	25	18	135
L118N 51+25W	.1	ND	10	15	45	140	4.48	1	26	18	148
L118N 51+50W	.1	ND	10	18	62	345	4.80	1	36	17	120
L118N 51+75W	.1	ND	15	16	63	952	5.00	ND	38	35	109
L118N 52+00W	.1	ND	5	16	60	1031	5.03	ND	39	33	114
L118N 52+25W	.1	ND	10	17	83	109	4.88	ND	40	13	72
L118N 52+50W	.1	ND	5	16	65	53	4.56	ND	41	8	96
L118N 52+75W	.1	ND	15	21	77	113	4.94	ND	50	12	78
L118N 53+00W	.1	ND	5	12	52	30	3.61	ND	26	14	128
L118N 53+25W	.1	4	5	22	66	224	4.67	4	60	23	92
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

GEOCHEMICAL ICP ANALYSIS

.500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER.
 THIS LEACH IS PARTIAL FOR MM.FE.CA.P.CR.MG.BA.TI.B.AL.NA.K.W.SI.ZR.CE.SM.Y.ND AND TA. AU DETECTION LIMIT BY ICP IS 3 PPM.
 - SAMPLE TYPE: ROCK CHIPS AU ANALYSIS BY AA FROM 10 GRAM SAMPLE.

DATE RECEIVED: SEPT 23 1986

DATE REPORT MAILED: *Sept 20/86*ASSAYER *D. Toy*... DEAN TOYE. CERTIFIED B.C. ASSAYER.

E & B EXPLORATION PROJECT - 5061 FILE # 86-2829

PAGE 1

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Hg	Ba	Ti	B	Al	Na	K	W	Au
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	PPM	%	%	%	PPM	PPM
KR-86-164	7	7626	11	54	.8	3	27	605	7.37	8	5	ND	1	229	1	2	2	184	1.05	.173	12	3	1.39	29	.17	10	1.73	.05	.10	1	490
KR-86-165	30	2239	17	80	.7	6	25	558	7.07	11	5	ND	1	83	1	2	2	255	.77	.141	13	17	1.34	53	.20	9	1.43	.02	.31	1	190
KR-86-166	23	5338	12	41	1.5	7	25	550	9.15	25	5	ND	2	43	1	2	2	292	1.17	.151	19	4	1.43	115	.21	7	1.81	.25	.10	1	340
KR-86-167	4	11970	2	25	.3	4	20	366	6.33	7	5	ND	1	701	1	2	2	168	1.14	.128	15	3	1.01	229	.15	9	1.92	.05	.20	1	800
KR-86-168	3	2199	13	24	.2	3	19	388	8.27	15	5	ND	1	54	1	2	2	178	.94	.168	17	5	.83	123	.15	9	1.13	.04	.10	1	205
KR-86-169	2	3257	8	30	.4	4	20	432	5.65	9	5	ND	1	354	1	2	2	146	.73	.092	10	3	.89	758	.16	6	1.36	.07	.15	1	190
KR-86-170	19	7840	12	45	.6	7	23	691	6.71	8	5	ND	1	23	1	2	2	167	.93	.133	12	6	.64	474	.06	4	1.33	.02	.07	1	210
STD C/AU-R	21	58	38	132	6.9	64	30	1003	3.93	40	20	8	33	47	17	16	21	61	.48	.106	37	56	.88	176	.08	37	1.73	.06	.13	14	515

VANGEOCHEM LAB LIMITED

MAIN OFFICE: 1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604)986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND
 IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -= NOT ANALYZED, *AU= AQUA REGA/AAS

COMPANY: E & B EXPLORATIONS REPORT#: 860470PA DATE RECEIVED: 86/09/17
 ATTENTION: L.SALEKEN & M.TINDALL JOB#: 860470 DATE COMPLETED: 86/09/23
 PROJECT: 5061-CB PD#5612 INVOICE#: 860470NA COPY SENT TO: VANCOUVER OFFICE

ANALYST *W. Rivers*

PAGE 1 OF 1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
FLDAT 1	.8	11	320	30	8	1718	7.01	1	4	15	85
86-MR-044	1.1	65	20	6	11	151	4.82	4	3	15	85
86-MR-045	1.3	50	5	5	6	248	4.06	6	2	22	62
86-MR-046	7.1	12	2880	34	7	14419	10.10	9	6	11	260
KR-86-138	1.3	27	10	10	54	171	3.59	1	6	26	68
KR-86-139	3.5	40	620	17	17	2398	5.48	3	5	20	234
KR-86-140	.8	14	90	26	15	1215	4.22	21	4	13	368
KR-86-141	1.2	10	5	10	18	106	3.28	ND	4	20	62
KR-86-142	1.5	17	120	13	24	796	3.68	1	3	16	101
KR-86-143	1.2	128	510	9	14	3407	3.19	3	7	13	43
KR-86-144	1.7	29	650	13	25	3526	3.87	1	5	16	35
KR-86-145	1.7	23	2400	15	17	13341	4.30	10	8	10	4
KR-86-146	1.6	18	550	12	21	1631	5.40	10	5	18	49
KR-86-147	1.8	18	860	17	13	4011	5.91	2	7	19	56
KR-86-148	2.1	27	1850	18	26	4779	6.03	6	7	15	32
KR-86-149	.6	5	10	18	17	126	4.83	ND	6	19	128
KR-86-150	.8	ND	10	16	28	175	4.32	ND	8	21	81
KR-86-151	.6	12	ND	26	9	148	5.61	12	7	16	325
KR-86-152	.6	ND	20	18	21	188	4.00	ND	5	13	94
KR-86-153	.1	ND	5	17	18	148	3.98	ND	4	4	102
KR-86-154	.4	3	154	23	23	3671	5.61	1	11	12	80
KR-86-155	4.3	18	390	22	30	7684	8.54	5	6	18	79
KR-86-156	.6	ND	80	21	31	843	4.94	ND	8	15	215
KR-86-157	.1	14	290	18	17	2093	5.40	ND	6	1	69
KR-86-158	5.5	24	1230	18	25	5223	4.87	5	6	26	230
KR-86-159	2.4	17	960	14	12	4116	5.39	1	7	24	54
KR-86-160	2.1	12	34	18	18	276	5.48	ND	5	29	231
KR-86-161	2.7	17	200	16	14	6019	1.48	3	9	23	142
KR-86-162	1.7	26	ND	7	27	270	2.87	1	5	27	137
KR-86-163	2.7	23	510	16	10	4335	3.38	2	7	31	132
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

RECEIVED
 SEP 24 1986
REGISTERED

VANGEOCHEM LAB LIMITED

MAIN OFFICE: 1521 PEMBERTON AVE. N.VANCOUVER B.C. V7P 2S3 PH:(604)986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH:(604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE. ND= NOT DETECTED. -= NOT ANALYZED. *AU= AQUA REGA/AAS

COMPANY: E & B EXPLORATIONS REPORT#: 860434PA DATE RECEIVED: 86/09/03
 ATTENTION: L.SALEKEN & M.TINDALL JOB#: 860434 DATE COMPLETED: 86/09/22
 PROJECT: 5061-CB P0#5589 INVOICE#: 860434NA COPY SENT TO: VANCOUVER OFFICE

ANALYST W. P. Rains

PAGE 1 OF 8

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L106N 70+25W	.1	ND	35	19	30	408	4.67	2	22	15	111
L106N 70+50W	.1	ND	20	50	62	1330	7.18	7	48	38	264
L106N 70+75W	.1	ND	15	15	28	322	4.01	1	19	15	107
L106N 71+00W	.1	7	5	5	22	57	3.13	1	5	4	51
L106N 71+25W	.1	ND	30	11	27	153	4.15	ND	17	10	119
L106N 71+50W	.1	ND	30	16	27	405	4.77	1	16	14	102
L106N 71+75W	.1	3	30	9	21	111	3.54	1	8	13	103
L106N 72+00W	.1	ND	30	12	23	199	3.77	1	13	15	116
L106N 72+25W	.1	8	35	20	24	633	4.75	1	21	19	119
L106N 72+50W	.1	ND	30	18	30	405	4.32	1	20	16	99
L106N 72+75W	.1	3	20	16	29	356	4.25	2	18	18	94
L106N 73+00W	.1	ND	5	11	23	282	2.15	ND	14	13	62
L108N 70+25W	.1	ND	25	22	28	448	4.90	3	19	12	116
L108N 70+50W	.1	ND	15	12	23	92	3.87	1	11	11	231
L108N 70+75W	.1	8	10	6	20	43	3.12	1	6	10	92
L108N 71+00W	.1	ND	5	10	21	121	4.12	ND	10	8	171
L108N 71+25W	.1	ND	15	12	22	61	5.12	ND	7	9	138
L108N 71+50W	.1	ND	40	22	24	763	4.95	2	20	16	113
L108N 71+75W	.1	3	20	16	24	455	4.10	1	16	15	99
L108N 72+00W	.1	10	50	13	21	354	3.83	1	14	13	89
L108N 72+25W	.1	6	15	14	24	233	3.85	2	20	18	78
L108N 72+50W	.1	7	30	12	27	210	3.47	1	18	16	85
L108N 72+75W	.1	9	20	14	26	296	3.70	1	18	20	84
L108N 73+00W	.1	5	10	13	25	293	3.62	1	15	17	82
L108N 73+25W	.1	7	20	13	29	135	2.62	1	17	20	66
L108N 73+50W	.1	11	10	12	27	57	2.97	1	16	14	66
L108N 73+75W	.1	14	10	6	19	43	2.11	1	9	15	55
L108N 74+00W	.1	10	15	6	15	59	1.63	ND	8	19	45
L110N 70+25W	.1	3	5	9	27	157	2.38	ND	15	15	57
L110N 70+50W	.1	ND	20	12	23	375	3.59	1	15	13	130
L110N 70+75W	.1	ND	20	10	25	3150	3.24	2	24	2	78
L110N 71+00W	.1	ND	5	9	29	187	3.41	ND	12	4	155
L110N 71+25W	.1	ND	20	11	24	140	4.54	2	10	7	176
L110N 71+50W	.1	ND	25	7	24	4061	2.52	2	20	ND	60
L110N 71+75W	.1	ND	15	23	40	2914	5.48	2	38	16	136
L110N 72+00W	.1	ND	10	8	20	1820	2.54	1	16	ND	62
L110N 72+25W	.1	ND	20	16	29	273	5.12	ND	17	13	254
L110N 72+50W	.1	ND	20	12	30	147	4.99	ND	12	9	222
L110N 72+75W	.1	5	30	12	24	207	4.25	2	13	12	106
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L110N 73+00W	.1	ND	ND	28	34	903	5.41	2	27	30	163
L110N 73+25W	.1	5	145	18	29	465	5.09	1	23	23	121
L110N 73+50W	.1	ND	20	13	27	270	5.37	2	17	18	167
L110N 73+75W	.1	ND	10	20	31	398	4.29	4	16	18	177
L110N 74+00W	.1	5	5	18	27	305	4.99	3	15	19	146
L112N 70+25W	.1	ND	25	16	27	487	5.30	2	16	16	164
L112N 70+50W	.1	ND	20	20	27	1129	4.65	2	22	15	123
L112N 70+75W	.1	ND	15	15	25	416	5.33	1	16	13	151
L112N 71+00W	.1	4	5	12	20	1273	3.45	4	18	7	93
L112N 71+25W	.1	ND	20	23	33	1127	5.58	2	27	19	154
L112N 71+50W	.1	ND	15	13	31	2268	4.01	1	31	15	98
L112N 71+75W	.1	ND	15	27	52	1572	6.50	3	46	29	189
L112N 72+00W	.1	ND	20	15	36	455	4.25	1	28	14	142
L112N 72+25W	.1	ND	20	16	38	466	4.54	1	30	15	143
L112N 72+50W	.1	ND	10	9	31	299	3.24	1	24	6	116
L112N 72+75W	.1	4	30	16	44	468	3.72	2	25	13	76
L112N 73+00W	.1	4	25	10	29	234	4.07	1	11	13	117
L112N 73+25W	.1	ND	20	11	28	165	4.74	1	10	13	172
L112N 73+50W	.1	4	20	3	13	2102	1.60	3	14	ND	31
L112N 73+75W	.1	4	20	3	14	1911	1.58	3	20	ND	32
L112N 74+00W	.1	ND	10	12	30	177	4.89	4	23	14	192
L114N 44+75W	.1	ND	5	11	38	84	3.15	ND	26	8	60
L114N 45+00W	.1	ND	5	11	51	42	3.77	ND	22	7	78
L114N 45+25W	.1	ND	ND	14	63	45	4.02	ND	30	10	93
L114N 45+50W	.1	ND	ND	13	68	36	4.10	ND	29	7	103
L114N 45+75W	.1	ND	ND	12	78	45	4.34	ND	30	11	79
L114N 46+00W	.1	ND	ND	14	90	52	4.87	ND	33	9	69
L114N 46+25W	.1	ND	ND	14	71	49	4.27	ND	30	11	75
L114N 46+50W	.1	ND	ND	14	67	58	4.55	ND	29	12	66
L114N 46+75W	.1	14	10	11	28	158	3.22	1	19	17	56
L114N 47+00W	.1	5	10	11	45	79	3.40	ND	24	9	66
L114N 47+25W	.1	ND	5	10	63	26	3.70	ND	21	8	102
L114N 47+50W	.1	ND	10	12	67	44	3.83	ND	34	12	77
L114N 47+75W	.1	4	5	8	50	30	3.11	ND	18	12	59
L114N 48+00W	.1	21	5	6	30	13	2.12	2	12	24	44
L114N 48+25W	.1	5	5	15	62	80	3.77	ND	42	32	76
L114N 48+50W	.1	11	5	12	41	100	3.32	1	23	30	95
L114N 48+75W	.8	14	190	29	22	5302	4.67	9	14	50	232
L114N 49+00W	.2	10	100	25	34	2768	5.22	6	22	39	194
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L114N 49+25W	.4	7	20	15	44	318	3.88	2	25	17	89
L114N 49+50W	.1	ND	15	12	46	137	3.52	1	26	15	61
L114N 49+75W	.1	8	10	10	36	100	3.08	1	19	16	79
L114N 70+25W	.4	ND	5	12	27	1366	3.31	2	26	15	86
L114N 70+50W	.1	ND	35	12	22	372	3.92	1	20	14	106
L114N 70+75W	.1	4	35	13	18	371	3.80	1	12	16	93
L114N 71+00W	.1	ND	20	11	19	254	3.87	1	12	14	162
L114N 71+50W	.1	ND	25	14	23	494	4.02	1	17	12	138
L114N 71+75W	.1	ND	20	12	22	405	4.00	1	14	13	119
L114N 72+00W	.1	3	55	16	24	650	4.25	1	18	11	75
L114N 72+25W	.1	ND	40	16	24	560	3.90	1	19	14	92
L114N 72+50W	.1	ND	35	19	28	812	4.50	2	21	14	96
L114N 72+75W	.1	4	45	17	27	661	4.34	2	21	13	72
L114N 73+00W	.1	3	25	13	23	1235	3.55	4	18	10	77
L114N 73+25W	.1	ND	15	15	25	1598	3.59	3	22	9	101
L114N 73+50W	.1	ND	15	18	33	1023	4.62	2	25	11	112
L114N 73+75W	.1	ND	15	15	23	702	3.65	3	20	11	121
L114N 74+00W	.1	ND	20	13	23	799	3.46	2	17	7	127
L116N 45+75W	.1	7	10	17	39	109	3.83	1	25	10	67
L116N 46+00W	.1	6	5	11	34	449	2.77	1	29	7	81
L116N 46+25W	.1	4	5	13	38	56	3.31	1	28	14	69
L116N 46+50W	.1	9	10	12	30	83	3.01	1	22	13	51
L116N 46+75W	.1	4	5	12	51	22	3.54	1	20	13	86
L116N 47+00W	.1	ND	5	15	70	43	4.23	ND	34	10	68
L116N 47+25W	.1	ND	5	15	69	41	4.49	ND	34	10	75
L116N 47+50W	.1	ND	5	16	63	64	4.30	ND	29	11	78
L116N 47+75W	.1	ND	5	11	48	32	3.60	ND	26	12	86
L116N 48+00W	.1	ND	5	16	45	34	3.87	ND	30	16	97
L116N 48+25W	.1	ND	10	14	57	49	3.93	ND	30	12	82
L116N 48+50W	.1	ND	5	13	52	36	3.85	ND	27	10	69
L116N 48+75W	.1	4	ND	9	43	23	3.20	1	16	15	89
L116N 49+00W	.1	ND	30	23	47	1123	5.95	1	37	11	145
L116N 49+25W	.1	4	10	17	42	1198	4.57	ND	27	13	120
L116N 49+50W	.1	ND	5	13	52	162	3.87	ND	28	12	101
L116N 49+75W	.1	6	10	21	42	939	5.37	2	24	19	161
L116N 50+00W	.1	3	15	18	41	464	4.59	ND	27	19	120
L116N 50+25W	.1	ND	5	14	48	73	3.97	ND	29	14	135
L116N 50+50W	.1	46	25	36	22	1276	6.31	3	19	60	99
L116N 50+75W	.1	ND	25	14	45	516	4.19	ND	30	14	169
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L118N 53+50W	.1	32	15	34	65	378	6.18	8	178	50	122
L118N 53+75W	.1	ND	10	20	64	248	4.81	2	62	24	300
L118N 54+00W	.1	ND	5	16	54	126	4.61	3	32	14	78
L118N 54+25W	.1	ND	10	14	46	90	3.85	1	31	13	84
L118N 54+50W	.1	6	5	11	39	48	3.35	ND	25	12	107
L118N 54+75W	.1	ND	5	18	82	125	5.01	ND	47	13	80
L118N 55+00W	.1	ND	5	14	57	125	4.26	ND	40	12	124
L118N 55+25W	.1	5	5	15	50	157	4.23	1	29	14	114
L118N 55+50W	.1	5	35	18	57	162	4.51	1	35	16	98
L118N 55+75W	.1	5	15	16	48	124	4.10	1	26	13	100
L118N 56+00W	.1	4	15	12	43	107	4.24	1	21	12	120
L118N 56+25W	.1	ND	15	15	52	138	4.78	ND	34	16	154
L118N 56+50W	.1	ND	25	12	49	139	4.47	1	30	15	134
L118N 56+75W	.1	ND	10	11	46	157	4.29	1	28	9	157
L118N 57+00W	.1	8	5	13	34	142	4.04	1	20	22	87
L118N 57+25W	.1	ND	5	19	82	189	4.66	1	83	12	108
L120N 46+50W	.1	ND	5	19	53	65	4.58	ND	51	19	98
L120N 46+75W	.1	4	5	11	37	45	3.15	ND	31	10	84
L120N 47+00W	.1	5	5	11	37	45	3.06	1	28	13	69
L120N 47+25W	.1	9	10	7	31	29	2.45	1	19	12	57
L120N 47+50W	.1	8	ND	11	49	33	3.16	1	40	12	67
L120N 47+75W	.1	5	ND	10	43	28	2.96	ND	26	12	61
L120N 48+00W	.1	ND	ND	12	56	48	3.72	ND	36	8	73
L120N 48+25W	.1	ND	ND	13	61	51	4.02	ND	36	4	79
L120N 48+50W	.1	ND	5	14	77	43	4.29	ND	35	12	83
L120N 48+75W	.1	ND	20	12	61	47	4.42	ND	32	7	101
L120N 49+00W	.1	6	5	10	45	201	2.97	1	23	13	92
L120N 49+25W	.1	ND	5	14	67	244	4.90	ND	34	13	126
L120N 49+50W	.1	ND	5	21	68	797	4.87	ND	48	6	84
L120N 49+75W	.1	ND	5	19	72	638	4.59	ND	49	11	78
L120N 50+25W	.1	ND	5	18	61	192	4.15	ND	30	9	132
L120N 50+50W	.1	ND	5	16	63	114	4.29	ND	40	8	78
L120N 50+75W	.1	ND	5	18	74	133	4.46	ND	41	8	78
L120N 51+00W	.1	ND	5	19	68	311	4.58	1	44	12	90
L120N 51+25W	.1	ND	5	16	65	109	4.41	1	40	11	114
L120N 51+50W	.1	ND	10	19	73	148	4.92	ND	46	9	104
L120N 51+75W	.1	ND	5	16	71	108	4.58	ND	36	7	115
L120N 52+00W	.1	ND	5	13	63	58	4.31	1	29	5	72
L120N 52+50W	.1	ND	5	15	66	69	3.98	1	50	8	54
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L120N 52+75W	.1	9	5	16	66	54	3.82	1	31	9	51
L120N 53+00W	.1	4	5	13	52	50	3.43	1	32	6	122
L120N 53+50W	.1	ND	5	13	53	49	3.50	1	27	6	134
L120N 53+75W	.1	5	ND	14	60	123	3.72	1	37	9	100
L120N 54+00W	.1	3	ND	18	63	77	4.24	1	36	9	75
L120N 54+25W	.1	4	5	17	73	89	4.16	1	43	11	73
L120N 54+75W	.1	3	10	17	68	59	4.02	1	39	9	58
L120N 55+25W	.1	4	5	18	65	117	4.05	1	38	14	77
L120N 55+50W	.1	9	5	13	49	41	3.37	1	26	10	52
L120N 55+75W	.1	6	5	12	35	47	3.22	2	19	10	58
L120N 57+75W	.1	11	ND	10	45	41	3.12	2	16	12	74
L120N 58+00W	.1	11	ND	9	38	35	2.80	2	14	13	66
L122N 47+25W	.1	9	ND	13	44	85	3.07	1	22	12	56
L122N 47+50W	.1	8	ND	14	47	86	3.29	1	24	12	61
L122N 47+75W	.3	3	ND	13	61	42	3.71	1	25	10	110
L122N 48+00W	.5	4	10	13	60	34	3.60	1	30	10	102
L122N 48+25W	.3	7	10	14	53	33	3.54	1	26	11	67
L122N 48+50W	.1	5	10	12	50	26	3.32	1	30	10	85
L122N 48+75W	.1	9	ND	11	34	38	2.89	1	20	10	53
L122N 49+00W	.5	11	ND	10	41	30	2.95	1	19	12	65
L122N 49+25W	.1	9	ND	12	35	33	2.83	1	25	12	46
L122N 49+50W	.1	9	ND	10	48	31	3.04	1	24	10	63
L122N 49+75W	.3	5	5	15	63	91	3.87	2	35	13	65
L122N 50+00W	.3	ND	5	14	61	191	3.83	1	34	11	97
L122N 50+25W	.1	5	20	14	55	216	3.68	1	25	9	63
L122N 50+50W	.1	9	10	16	58	206	3.86	1	30	11	58
L122N 50+75W	.1	ND	5	13	43	187	3.58	1	31	10	70
L122N 51+00W	.1	5	5	13	42	177	3.58	1	31	10	66
L122N 51+25W	.7	3	10	15	52	346	3.43	ND	40	10	63
L122N 51+50W	.1	6	5	13	56	66	3.71	1	28	12	68
L122N 51+75W	.1	ND	ND	18	63	123	4.05	1	37	13	64
L122N 52+00W	.1	4	ND	14	54	122	3.72	1	31	11	63
L122N 52+25W	.1	ND	ND	20	71	103	4.41	ND	44	10	67
L122N 52+50W	.1	ND	ND	20	67	98	4.40	ND	41	10	111
L122N 52+75W	.1	3	ND	14	63	57	3.97	2	29	10	126
L122N 53+75W	.1	ND	ND	23	55	230	5.01	ND	46	12	142
L122N 54+00W	.1	5	ND	14	49	74	3.85	1	27	11	65
L122N 54+25W	.1	5	ND	17	72	84	4.31	1	34	12	63
L122N 54+50W	.1	ND	ND	12	49	49	3.29	ND	30	6	93
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L122N 54+75W	.1	5	ND	14	58	47	3.92	1	28	12	68
L122N 55+00W	.1	ND	ND	18	57	77	4.15	ND	54	18	119
L122N 55+25W	.1	ND	ND	18	56	76	4.07	ND	52	18	117
L122N 55+50W	.1	ND	ND	14	62	48	3.75	1	45	16	92
L122N 55+75W	.1	5	ND	16	67	92	4.45	1	42	17	92
L122N 56+00W	.1	3	ND	13	68	43	4.08	1	34	14	86
L122N 56+25W	.1	ND	ND	12	60	48	3.87	1	34	15	100
L122N 56+50W	.1	6	ND	11	58	57	3.82	2	27	15	100
L122N 56+75W	.1	11	ND	7	48	21	2.65	2	15	13	75
L122N 57+00W	.1	16	ND	6	36	14	1.92	2	10	12	58
L122N 57+25W	.1	ND	ND	15	71	55	4.25	1	44	15	82
L122N 57+50W	.1	6	ND	13	65	44	3.79	1	36	12	80
L122N 57+75W	.1	13	ND	9	43	20	2.52	2	14	13	73
L122N 58+00W	.1	6	20	12	47	70	3.67	1	27	19	112
L124N 49+00W	.1	6	20	11	46	32	3.34	1	24	11	86
L124N 49+25W	.1	9	5	11	44	31	3.16	1	23	11	84
L124N 49+50W	.1	8	5	11	46	35	3.13	1	21	10	59
L124N 49+75W	.1	4	5	15	53	45	3.79	1	25	11	66
L124N 50+00W	.1	4	5	14	53	45	3.75	1	26	12	63
L124N 50+25W	.1	8	5	11	42	45	3.04	1	26	13	51
L124N 50+50W	.1	ND	5	16	60	118	4.05	1	33	17	57
L124N 50+75W	.1	ND	10	16	59	256	4.08	ND	40	16	63
L124N 51+00W	.1	ND	5	21	70	265	4.89	ND	45	16	88
L124N 51+25W	.1	ND	10	20	68	250	4.70	ND	45	19	86
L124N 51+50W	.1	8	ND	9	36	23	2.97	1	15	7	55
L124N 51+75W	.1	8	ND	10	34	45	2.70	1	18	5	48
L124N 52+00W	.1	4	ND	11	50	45	3.44	1	20	4	62
L124N 52+25W	.1	5	ND	10	37	67	3.04	1	19	8	57
L124N 52+50W	.1	3	ND	12	44	75	3.45	1	24	7	64
L124N 52+75W	.1	ND	ND	12	41	40	3.25	1	20	3	75
L124N 53+00W	.1	ND	ND	13	46	49	3.66	ND	23	4	65
L124N 53+25W	.1	ND	ND	11	51	49	3.37	1	24	3	70
L124N 53+50W	.1	ND	ND	13	44	108	3.37	ND	24	5	51
L124N 53+75W	.1	ND	ND	16	64	168	4.26	ND	36	3	66
L124N 54+00W	.1	ND	ND	12	57	42	3.83	ND	24	7	105
L124N 55+00W	.1	ND	ND	14	66	56	4.12	ND	30	8	92
L124N 55+25W	.1	ND	ND	12	78	30	4.37	1	29	6	87
L124N 55+50W	.1	ND	10	13	31	112	3.74	ND	19	3	61
L124N 55+75W	.1	ND	10	11	43	150	3.33	ND	26	2	53
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L124N 56+00W	.1	8	ND	9	28	83	2.91	ND	13	1	41
L124N 56+25W	.1	ND	ND	11	48	37	3.59	ND	21	4	72
L124N 56+50W	.1	5	ND	12	42	45	3.59	ND	17	7	51
L124N 56+75W	.1	ND	10	13	61	35	3.69	ND	34	5	60
L124N 57+00W	.1	ND	5	9	25	19	3.37	ND	8	8	77
L124N 57+25W	.1	ND	ND	10	13	15	3.54	ND	6	7	96
L124N 57+50W	.1	ND	15	11	45	31	3.54	ND	19	5	57
L124N 57+75W	.1	ND	ND	9	19	17	3.40	ND	13	4	79
L124N 58+00W	.1	ND	ND	10	47	26	3.47	ND	19	6	46
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

VANGEOCHEM LAB LIMITED

MAIN OFFICE: 1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604) 986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604) 251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND
 IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -= NOT ANALYZED, *AU= GEOCHEM

COMPANY: E & B EXPLORATIONS
 ATTENTION:
 PROJECT: 5061-CB P0#5589

REPORT#: 860435PA DATE RECEIVED: 86/09/03
 JOB#: 860435 DATE COMPLETED: 86/09/16
 INVOICE#: 860435NA COPY SENT TO:

ANALYST W. Rows

PAGE 1 OF 1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L96N 46+25W	.1	5	15	9	27	89	2.80	3	18	13	58
L112N 44+00W	.1	ND	10	12	36	62	2.68	1	24	12	60
L112N 44+25W	.1	ND	5	11	49	24	3.35	ND	23	11	82
L112N 44+50W	.3	3	5	9	26	23	2.35	ND	14	9	44
L112N 44+75W	.1	ND	5	13	40	53	3.20	ND	25	13	56
L112N 45+00W	.1	ND	20	10	40	39	3.10	ND	24	14	52
L112N 45+25W	.2	ND	10	10	53	34	3.28	ND	24	12	56
L112N 45+50W	.3	ND	5	10	52	34	3.38	ND	24	14	66
L112N 45+75W	.2	ND	5	10	52	35	3.27	ND	23	13	57
L112N 46+00W	.2	ND	5	10	49	28	3.10	ND	23	12	51
L112N 46+25W	.3	5	15	11	44	30	3.05	ND	23	13	46
L112N 46+50W	.1	3	10	9	37	29	2.81	ND	23	12	58
L112N 46+75W	.5	3	10	8	30	27	2.70	1	21	15	64
L112N 47+00W	.3	4	5	9	36	27	2.53	ND	20	13	51
L112N 47+25W	.3	4	5	10	39	33	2.77	ND	22	14	50
L112N 47+50W	.2	4	10	11	47	37	3.26	ND	26	15	57
L112N 47+75W	.2	ND	5	10	44	25	3.26	1	23	15	69
L112N 48+00W	.1	8	5	17	67	116	4.15	ND	48	19	61
L112N 48+25W	.1	3	10	9	31	22	2.75	1	24	15	61
L112N 48+50W	.3	ND	20	13	50	42	3.60	1	36	16	64
L112N 48+75W	.3	ND	15	10	38	25	2.95	1	23	16	72
L112N 49+00W	.3	4	5	9	30	44	2.85	ND	20	15	63
L112N 49+25W	.2	ND	5	13	42	63	3.63	1	25	16	55
L112N 49+50W	.3	ND	5	8	31	15	2.57	ND	20	16	68
L112N 49+75W	.4	3	5	11	42	25	3.02	1	23	16	69
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

VANGEOCHEM LAB LIMITED

Paul Stealy

MAIN OFFICE: 1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604)986-5211
BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -= NOT ANALYZED, *AU= GEOCHEM

COMPANY: E & B EXPLORATIONS REPORT#: 860411PA DATE RECEIVED: 86/08/27
ATTENTION: L. SALAKEN & M. TINDALL JOB#: 860411 DATE COMPLETED: 86/09/02
PROJECT: 5061-CARIBOO BELL INVOICE#: 860411NA COPY SENT TO: VANC. OFFICE

ANALYST *W. P. Reed*

PAGE 1 OF 1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
86 MR-007	.8	21	200	135	10	1027	3.70	10	19	29	562
86 MR-008	.5	23	200	11	5	305	4.51	12	3	22	42
86 MR-009	1.2	51	1200	12	9	421	3.33	101	3	19	43
86 MR-010	1.2	82	410	9	18	3379	6.84	8	5	12	40
86 MR-011	.4	32	240	23	18	908	16.86	7	6	12	53
86 MR-012	2.7	ND	1200	57	18	10706	14.19	2	2	11	68
86 MR-013	4.6	ND	1400	112	10	19244	29.62	4	2	8	180
86 MR-014	4.1	96	1300	44	29	5752	6.12	7	14	14	292
86 MR-015	1.1	40	75	9	5	550	3.47	7	2	39	60
86 MR-016	8.6	28	1165	25	7	15048	7.38	3	5	42	255
86 MR-017	.8	45	70	5	5	405	2.95	4	1	43	137
86 MR-018	.8	24	ND	11	7	319	4.22	12	3	88	107
86 MR-019	7.1	7	790	13	7	12128	3.12	2	2	47	70
86 MR-020	5.8	25	15	20	8	9995	5.33	9	3	24	349
86 MR-021	.8	22	ND	19	9	354	3.55	1	6	18	66
86 MR-022	1.7	66	20	22	8	105	4.55	4	6	155	1194
86 MR-023	1.1	38	15	18	5	880	2.87	12	4	20	95
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

* note - MR007 - MR009 are high in W, suggest assay if there is any interest in W.

Len Salaken

VANGEOCHEM LAB LIMITED

MAIN OFFICE: 1521 PEMBERTON AVE. N.VANCOUVER B.C. V7P 2S3 PH:(604)986-5211
BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH:(604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -= NOT ANALYZED, *AU= GEOCHEM

COMPANY: E&B EXPLORATIONS REPORT#: 860397PA DATE RECEIVED: 86/08/22
ATTENTION: L.SALEKEN & M.TINDALL JOB#: 860397 DATE COMPLETED: 86/08/29
PROJECT: 5061-CB PO# 5562 INVOICE#: 860397NA COPY SENT TO: VANC.OFFICE

ANALYST W. Reems

PAGE 1 OF 1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE Z	MO PPM	NI PPM	PB PPM	ZN PPM
86 MR-006	1.1	20	ND	6	15	85	1.97	8	8	22	135
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

VANGEOCHEM LAB LIMITED

MAIN OFFICE: 1521 PEMBERTON AVE. N.VANCOUVER B.C. V7P 2S3 PH:(604)986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH:(604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -- NOT ANALYZED, *AU= GEOCHEM

COMPANY: E&B EXPLORATIONS REPORT#: 860425PA DATE RECEIVED: 86/09/02
 ATTENTION: L.SALEKEN & M.TINDALL JOB#: 860425 DATE COMPLETED: 86/09/05
 PROJECT: CB-5061 PO#5587 INVOICE#: 860425NA COPY SENT TO: VANCOUVER OFFICE

ANALYST W. Jones

PAGE 1 OF 1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
86MR-024	14.3	18	1650	44	10	22243	7.10	13	6	98	590
86MR-025	3.1	31	1060	18	8	8672	4.44	16	5	28	53
86MR-026	2.4	19	240	19	10	6736	4.23	2	3	26	269
86MR-027	3.4	9	3630	23	21	13600	14.88	2	8	14	29
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

VANGEOCHEM LAB LIMITED

MAIN OFFICE: 1521 PEMBERTON AVE. N.VANCOUVER B.C. V7P 2S3 PH: (604)986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND
 IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -- NOT ANALYZED, *AU= GEOCHEM

COMPANY: E & B EXPLORATIONS REPORT#: 860440PA DATE RECEIVED: 86/09/05
 ATTENTION: L.SALEKEN & M.TINDALL JOB#: 860440 DATE COMPLETED: 86/09/09
 PROJECT: 5061 CB-PO#5600 INVOICE#: 860440NA COPY SENT TO: VANCOUVER OFFICE

ANALYST W. Reeves

PAGE 1 OF 1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
BR-86-001	4.0	15	195	35	9	4491	4.68	109	4	39	168
BR-86-002	.7	6	105	29	37	2870	5.75	12	12	21	119
BR-86-003	6.6	26	75	36	8	7581	3.77	49	3	64	291
KR-86-131	.1	12	ND	18	18	193	4.59	6	28	6	209
KR-86-132	.6	21	ND	11	9	493	4.10	19	4	17	79
KR-86-133	.1	3	5	26	23	171	5.63	1	16	11	89
KR-86-134	.2	8	675	20	9	2350	5.09	ND	2	54	272
KR-86-135	1.3	ND	185	40	11	4173	9.52	56	5	11	54
KR-86-136	.8	3	235	24	18	2003	6.09	19	5	12	49
KR-86-137	.7	ND	475	10	6	1060	13.14	23	1	5	23
86-MR-034	2.8	12	885	28	10	9473	6.88	2	6	12	88
86-MR-035	1.2	5	375	19	10	10793	5.43	3	6	19	45
86-MR-036	.4	ND	75	24	7	4785	7.05	8	3	7	54
86-MR-037	.8	ND	2085	20	18	8775	6.93	1	8	12	44
86-MR-038	1.7	3	1845	24	10	8305	7.23	4	9	10	54
86-MR-039	.7	9	2085	15	15	9729	4.67	2	4	14	39
86-MR-040	1.9	13	605	33	9	11128	3.95	7	5	19	219
86-MR-041	2.3	11	65	20	10	5873	4.09	4	1	15	64
86-MR-042	85.0	ND	15385	55	14	73795	12.90	12	11	4	97
86-MR-043	.1	ND	5	15	57	246	3.89	ND	78	8	134
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

Au analyses by fire assay/AAS finish

*Pack
1/5/86*

VANGEOCHEM LAB LIMITED

MAIN OFFICE: 1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604)986-5211
BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -- NOT ANALYZED, +AU= GEOCHEM

COMPANY: E&B EXPLORATIONS REPORT#: 860397PA DATE RECEIVED: 86/08/22
ATTENTION: L.SALEKEN & M.TINDALL JOB#: 860397 DATE COMPLETED: 86/08/29
PROJECT: 5061-CB PO# 5562 INVOICE#: 860397NA COPY SENT TO: VANC.OFFICE

ANALYST W. Reems

PAGE 1 OF 1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
86 MR-006	1.1	20	ND	6	15	85	1.97	8	8	22	135
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

RECEIVED
SEP - 2 1986
RECEIVED

VANGEOCHEM LAB LIMITED

1!)testing

MAIN OFFICE: 1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604)986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -- NOT ANALYZED, *AU= GEOCHEM

COMPANY: E & B EXPLORATIONS REPORT#: 860411PA DATE RECEIVED: 86/08/27
 ATTENTION: L. SALAKEN & M. TINDALL JOB#: 860411 DATE COMPLETED: 86/09/02
 PROJECT: 5061-CARIBOO BELL INVOICE#: 860411NA COPY SENT TO: VANC. OFFICE

ANALYST W. Reeves

PAGE 1 OF 1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
86 MR-007	.8	21	200	135	10	1027	3.70	10	19	29	562
86 MR-008	.5	23	200	11	5	305	4.51	12	3	22	42
86 MR-009	1.2	51	1200	12	9	421	3.33	101	3	19	43
86 MR-010	1.2	82	410	9	18	3379	6.84	8	5	12	40
86 MR-011	.4	32	240	23	18	908	16.86	7	6	12	53
86 MR-012	2.7	ND	1200	57	18	10706	14.19	2	2	11	68
86 MR-013	4.6	ND	1400	112	10	19244	29.62	4	2	8	180
86 MR-014	4.1	96	1300	44	29	5752	6.12	7	14	14	292
86 MR-015	1.1	40	75	9	5	550	3.47	7	2	39	60
86 MR-016	8.6	28	1165	25	7	15048	7.38	3	5	42	255
86 MR-017	.8	45	70	5	5	405	2.95	4	1	43	137
86 MR-018	.8	24	ND	11	7	319	4.22	12	3	88	107
86 MR-019	7.1	7	790	13	7	12128	3.12	2	2	47	70
86 MR-020	5.8	25	15	20	8	9995	5.33	9	3	24	349
86 MR-021	.8	22	ND	19	9	354	3.55	1	6	18	66
86 MR-022	1.7	66	20	22	8	105	4.55	4	6	155	1194
86 MR-023	1.1	38	15	18	5	880	2.87	12	4	20	95
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

* note - MR007 - MR009 are high in W, suggest assay if there is any interest in W.

VANGEOCHEM LAB LIMITED

Karl Stealey

MAIN OFFICE: 1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604)986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -= NOT ANALYZED, +AU= GEOCHEM

COMPANY: E&B EXPLORATIONS
 ATTENTION: L.SALEKEN & M.TINDALL
 PROJECT: 5061-CB PO# 5562

REPORT#: 860398PA
 JDB#: 860398
 INVOICE#: 860398NA

DATE RECEIVED: 86/08/22
 DATE COMPLETED: 86/08/28
 COPY SENT TO: VANC.OFFICE

ANALYST *W. Reeves*

PAGE 1 OF 13

SAMPLE NAME	AG PPM	AS PPM	AU #PPB	CO PPM	CR PPM	CU PPM	FE I	MO PPM	NI PPM	PB PPM	ZN PPM
L76N 53+50W	.2	7	ND	16	31	30	3.34	1	20	12	136
L86N 50+00W	.1	4	ND	7	24	23	2.46	1	16	11	83
L86N 50+25W	.4	9	20	16	28	313	3.84	4	20	21	265
L86N 50+50W	.2	4	5	13	27	136	2.90	2	17	13	216
L86N 50+75W	.2	8	10	20	44	209	3.28	4	30	16	230
L86N 51+00W	.3	8	10	22	39	279	3.27	7	27	18	164
L86N 51+50W	.3	7	ND	12	34	89	3.37	7	20	16	408
L86N 51+75W	.3	8	5	15	30	145	3.02	3	22	17	200
L86N 52+75W	.2	6	ND	9	24	34	2.42	3	12	16	151
L86N 53+00W	.4	7	ND	7	21	29	2.56	2	9	16	91
L86N 53+25W	.4	6	ND	14	27	91	3.80	2	18	15	103
L86N 53+50W	.6	6	ND	15	19	92	4.04	2	14	18	145
L86N 54+00W	.6	6	ND	14	33	135	4.19	2	19	19	194
L86N 54+25W	.4	5	ND	10	26	109	2.75	5	16	15	64
L86N 54+50W	.6	11	ND	18	19	189	4.35	4	14	17	86
L86N 54+75W	.5	3	15	10	22	108	3.68	2	9	16	123
L86N 55+00W	.6	11	10	12	22	86	4.27	1	10	19	193
L86N 55+25W	.6	ND	10	11	19	91	3.72	1	11	16	191
L86N 55+50W	.4	11	ND	13	20	103	3.62	1	15	16	108
L86N 55+75W	.6	9	ND	8	18	38	2.63	1	9	15	84
L86N 56+00W	.9	ND	5	10	21	43	2.75	2	18	15	124
L86N 56+25W	.8	6	ND	11	23	48	2.90	1	14	15	101
L86N 56+50W	.7	3	ND	10	21	35	3.07	2	12	18	148
L86N 56+75W	1.1	9	ND	12	24	74	4.23	2	13	20	124
L86N 57+00W	.7	6	ND	8	19	33	2.59	1	8	15	80
L86N 57+25W	.6	7	25	11	22	53	2.90	1	17	17	108
L86N 57+50W	.5	4	ND	9	22	74	2.37	1	12	15	80
L86N 57+75W	.5	3	ND	11	35	34	2.65	1	29	17	80
L86N 58+00W	.5	7	ND	14	22	67	3.64	3	12	19	82
L86N 58+50W	.6	5	ND	8	22	16	2.20	1	12	16	71
L86N 59+00W	.4	3	ND	8	24	18	2.45	1	15	19	94
L86N 59+25W	.5	5	5	8	24	29	2.35	2	16	17	49
L86N 59+50W	.4	5	ND	9	27	43	2.38	1	19	16	46
L86N 59+75W	.3	7	ND	7	22	21	2.02	1	13	14	57
L86N 60+25W	.4	8	ND	6	18	21	1.69	1	12	15	61
L86N 60+50W	.4	5	ND	16	36	32	3.45	1	20	18	126
L86N 60+75W	.5	8	ND	5	14	15	1.14	1	7	13	26
L88N 50+75W	.5	4	ND	7	19	43	2.20	2	10	18	145
L88N 51+00W	.5	8	15	10	23	87	3.11	2	13	18	67
DETECTION LIMIT	.1	3	+5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE I	MO PPM	NI PPM	PB PPM	ZN PPM
L88N 51+25W	.2	3	20	8	19	73	2.60	2	9	11	56
L88N 51+50W	.2	4	20	10	17	77	2.82	1	11	12	68
L88N 51+75W	.2	3	20	9	18	87	2.64	2	11	13	83
L88N 52+00W	.2	3	30	9	19	101	2.82	2	10	13	78
L88N 52+25W	.1	5	35	9	19	81	2.28	1	12	14	48
L88N 52+50W	.1	8	40	9	21	78	2.42	1	14	13	53
L88N 52+75W	.5	8	45	9	17	88	2.99	2	7	18	89
L88N 53+00W	.5	11	30	10	17	102	3.16	3	9	19	86
L88N 53+25W	.5	4	10	12	21	105	2.72	1	14	15	147
L88N 53+50W	.5	8	20	11	17	110	2.35	2	13	13	98
L88N 53+75W	.5	6	10	11	22	73	2.64	1	15	12	106
L88N 54+00W	.3	5	10	12	24	81	2.84	1	18	13	118
L88N 54+25W	.4	4	ND	11	31	27	2.02	1	24	11	153
L88N 54+50W	.3	12	20	12	19	139	3.18	2	11	15	56
L88N 54+75W	.3	4	ND	9	19	68	2.10	1	12	11	92
L88N 55+00W	.2	10	20	10	17	73	2.58	2	11	12	45
L88N 55+25W	.2	6	10	10	18	84	2.60	1	12	14	61
L88N 55+50W	.1	11	20	15	21	177	3.00	3	15	14	78
L88N 55+75W	.1	10	10	15	27	198	3.63	4	19	15	83
L88N 56+00W	.1	10	5	12	25	170	3.35	4	16	15	76
L88N 56+25W	.1	10	25	14	25	186	3.51	3	24	14	77
L88N 56+50W	.1	10	10	14	25	183	3.45	3	20	16	75
L88N 56+75W	.1	10	20	17	24	208	3.42	4	19	15	78
L88N 57+00W	.1	9	10	13	18	77	3.06	1	11	12	47
L88N 57+25W	.1	4	ND	11	25	95	3.08	1	17	10	82
L88N 57+50W	.1	6	10	11	22	95	2.95	1	16	11	80
L88N 57+75W	.1	5	10	12	21	100	2.78	1	14	11	75
L88N 58+00W	.1	7	10	11	20	96	2.68	1	13	12	71
L88N 58+25W	.1	7	5	10	23	74	2.54	1	15	11	91
L88N 58+50W	.1	4	10	22	43	366	4.64	1	35	20	192
L88N 60+00W	.1	5	ND	19	40	192	4.12	3	27	17	263
L88N 60+25W	.1	6	ND	18	37	159	3.88	2	22	16	272
L90N 51+25W	.1	8	ND	7	19	40	2.77	2	9	14	114
L90N 51+50W	.1	6	ND	6	19	35	2.67	2	8	13	105
L90N 51+75W	.1	4	ND	4	12	15	1.43	2	2	9	61
L90N 52+00W	.1	5	ND	11	20	47	2.50	3	11	13	122
L90N 52+25W	.1	5	10	11	23	57	3.34	2	13	13	119
L90N 52+50W	.1	7	10	10	23	63	3.20	1	13	17	124
L90N 52+75W	.1	7	ND	13	28	139	3.06	2	15	16	108
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE I	MO PPM	NI PPM	PB PPM	ZN PPM
L90N 53+00W	.3	9	ND	8	20	41	2.57	1	11	14	96
L90N 53+25W	.2	7	ND	10	23	55	3.20	1	11	15	123
L90N 53+50W	.5	5	5	8	19	48	2.72	1	11	14	135
L90N 53+75W	.1	ND	ND	14	29	85	4.16	2	25	22	191
L90N 54+00W	.3	5	5	11	19	61	2.93	1	14	15	136
L90N 54+25W	.4	7	15	9	17	183	3.02	1	8	14	102
L90N 54+50W	.3	7	5	10	18	57	2.52	1	11	13	124
L90N 54+75W	.1	6	ND	12	14	127	2.53	1	11	16	175
L90N 55+00W	.4	6	15	12	20	93	3.19	1	12	14	129
L90N 55+25W	.5	5	5	12	20	94	3.16	1	13	14	129
L90N 55+50W	.5	4	15	10	17	49	2.77	1	6	12	180
L90N 55+75W	.6	10	40	14	23	231	3.42	3	19	16	148
L90N 56+00W	.4	7	15	7	15	42	2.52	1	4	10	65
L90N 56+25W	.4	6	ND	6	15	31	2.08	1	4	10	72
L90N 56+50W	.3	11	ND	10	19	67	2.50	1	9	9	104
L90N 56+75W	.2	11	5	10	22	108	2.93	1	13	12	84
L90N 57+25W	.6	9	20	12	24	3865	2.82	3	19	16	137
L90N 57+50W	.5	6	ND	13	19	81	2.80	1	9	13	160
L90N 57+75W	.5	9	ND	18	23	223	3.32	2	16	16	103
L90N 58+00W	.3	15	35	22	31	437	4.46	4	19	19	115
L90N 58+25W	.3	10	25	18	27	238	3.80	5	21	15	90
L90N 58+50W	.1	8	ND	10	21	49	3.02	2	12	11	91
L90N 58+75W	.1	7	5	10	22	47	3.02	2	8	11	93
L90N 59+00W	.2	8	ND	13	21	101	3.05	1	16	13	85
L90N 59+25W	.1	6	10	14	24	111	2.87	1	12	11	141
L90N 59+50W	.2	6	10	13	23	145	2.87	2	12	11	108
L90N 59+75W	.2	6	10	13	23	139	2.92	1	15	12	114
L90N 60+00W	.2	7	20	15	25	768	3.58	1	20	15	151
L90N 60+25W	.6	7	15	17	28	968	3.96	3	20	15	127
L90N 60+50W	.2	8	15	17	29	751	3.93	4	20	15	92
L92N 50+25W	.1	ND	ND	8	35	80	2.15	2	11	8	80
L92N 50+50W	.1	8	5	12	31	165	3.16	3	18	13	55
L92N 50+75W	.1	11	15	13	31	254	4.39	4	17	13	66
L92N 51+00W	.1	8	10	17	30	254	4.38	4	20	18	84
L92N 51+25W	.1	9	10	6	22	59	3.11	3	8	13	63
L92N 51+50W	.1	7	35	10	28	150	3.67	4	17	12	81
L92N 51+75W	.1	9	25	14	30	222	3.66	3	19	15	59
L92N 52+00W	.2	4	10	8	25	73	2.97	2	10	12	69
L92N 52+25W	.1	6	25	12	28	293	3.69	3	19	15	73
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE I	MO PPM	NI PPM	PB PPM	ZN PPM
L92N 52+50W	.1	13	20	25	25	412	5.03	2	19	28	159
L92N 52+75W	.1	5	10	18	26	233	4.13	1	17	20	108
L92N 53+00W	.1	10	20	22	25	347	4.66	2	16	22	142
L92N 53+25W	.2	4	30	14	31	181	4.00	1	20	19	92
L92N 53+50W	.1	4	40	16	33	260	4.41	2	20	21	99
L92N 53+75W	.4	5	15	14	30	162	4.10	1	17	21	106
L92N 54+00W	.5	7	15	18	48	5764	4.72	3	42	24	441
L92N 54+25W	.6	10	25	14	27	881	3.56	4	12	19	95
L92N 54+50W	.1	5	15	17	38	1973	4.08	5	27	21	166
L92N 54+75W	.5	5	15	12	25	479	3.34	2	13	15	76
L92N 55+00W	.2	6	15	12	26	116	3.58	1	13	15	124
L92N 55+25W	.7	7	20	13	28	2789	3.63	2	14	18	95
L92N 55+50W	1.4	9	30	31	63	9153	6.61	7	53	36	291
L92N 55+75W	.8	6	ND	12	25	199	3.39	1	12	19	188
L92N 56+00W	.9	5	15	15	30	125	3.81	1	18	21	191
L92N 56+25W	.7	5	ND	7	20	61	2.46	ND	8	15	109
L92N 56+75W	.6	7	10	22	45	3188	4.67	18	32	24	132
L92N 57+00W	.6	8	15	17	26	551	3.68	3	16	17	112
L94N 50+00W	1.5	7	20	41	70	5810	6.80	12	53	36	448
L94N 50+25W	.7	5	85	15	29	589	3.40	3	17	19	88
L94N 50+50W	.8	6	ND	9	33	296	2.49	3	18	16	55
L94N 50+75W	.6	3	10	6	26	50	2.43	1	14	15	63
L94N 51+25W	.6	6	10	6	33	42	2.36	1	16	14	61
L94N 51+50W	.7	6	ND	8	36	27	2.45	1	19	15	82
L94N 51+75W	.5	4	30	12	34	258	3.48	1	25	17	68
L94N 52+00W	.4	4	25	9	28	96	2.74	1	17	14	54
L94N 52+25W	.6	ND	35	13	27	205	3.52	2	24	19	61
L94N 52+50W	.9	6	20	12	31	157	3.97	2	24	19	134
L94N 52+75W	.5	6	25	8	24	76	3.48	2	12	17	65
L94N 53+00W	.7	5	5	8	37	117	3.15	2	14	15	104
L94N 53+25W	.4	4	20	9	25	1057	3.28	2	13	13	68
L94N 53+50W	.5	6	10	19	39	3935	4.18	4	29	22	136
L94N 53+75W	.8	7	5	11	27	286	3.71	2	16	21	116
L94N 54+00W	.6	8	50	11	21	691	3.03	2	12	17	53
L94N 54+25W	.5	5	15	10	27	286	3.39	2	19	19	70
L94N 54+50W	2.1	ND	35	29	76	891	6.90	1	122	30	170
L94N 54+75W	.5	3	15	8	14	105	3.52	ND	9	15	50
L94N 55+00W	.3	4	10	8	24	135	3.93	1	12	18	63
L94N 55+25W	.5	5	ND	4	15	175	2.10	ND	5	14	32
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPH	AS PPH	AU *PPB	CO PPH	CR PPH	CU PPH	FE %	MO PPH	NI PPH	PB PPH	ZN PPH
L106N 39+00W	.1	ND	ND	17	60	204	4.46	2	41	18	95
L106N 39+25W	.2	6	ND	15	55	174	4.05	2	36	17	84
L106N 39+50W	.3	8	5	14	49	179	3.58	1	32	15	73
L106N 39+75W	.2	10	ND	14	48	207	3.59	2	35	15	76
L106N 40+00W	.3	9	ND	14	45	182	3.41	1	28	15	68
L106N 40+25W	.2	6	ND	12	48	99	3.41	2	26	13	65
L106N 40+50W	.1	5	ND	11	45	70	3.27	1	24	10	61
L106N 40+75W	.1	6	ND	13	49	115	3.61	2	28	12	59
L106N 41+00W	.1	ND	ND	17	60	458	4.48	3	46	21	103
L106N 41+25W	.1	5	ND	11	40	71	3.30	1	24	9	86
L106N 41+50W	.1	5	5	13	60	46	3.75	1	31	11	59
L106N 41+75W	.1	7	5	16	59	186	3.96	5	32	14	84
L106N 42+00W	.1	6	ND	13	49	128	3.46	5	27	14	57
L106N 42+25W	.1	8	ND	21	74	178	4.64	2	51	17	86
L106N 42+50W	.1	7	ND	22	83	109	4.78	1	56	13	75
L106N 42+75W	.1	6	ND	19	58	103	3.97	1	46	15	65
L106N 43+00W	.1	5	ND	22	64	116	4.42	1	49	16	73
L106N 43+25W	.1	6	ND	13	42	31	3.61	1	28	12	80
L106N 43+50W	.1	4	ND	12	40	32	3.54	1	28	12	109
L106N 43+75W	.1	6	ND	15	46	37	3.94	1	28	13	63
L106N 44+00W	.1	ND	ND	15	48	38	4.06	1	37	14	66
L106N 44+50W	.3	4	ND	12	37	51	3.14	1	24	13	91
L106N 44+75W	.4	8	5	11	29	49	3.23	ND	13	10	44
L106N 45+00W	.4	12	20	12	26	52	3.05	1	15	9	40
L106N 45+25W	.2	ND	ND	14	47	49	3.96	ND	31	14	66
L106N 45+50W	.1	3	ND	13	47	47	3.93	ND	31	13	62
L106N 45+75W	.1	4	ND	16	45	62	4.26	1	40	17	72
L106N 46+00W	.6	10	5	13	38	135	3.54	ND	26	17	117
L106N 46+25W	.4	5	ND	13	38	140	3.59	ND	26	20	112
L106N 46+50W	.5	6	ND	12	35	123	3.30	ND	23	15	112
L106N 46+75W	.6	ND	ND	14	40	141	3.69	ND	26	15	103
L106N 47+00W	.1	ND	ND	17	40	52	4.07	ND	35	22	221
L106N 47+25W	.1	ND	ND	16	48	53	4.40	ND	35	19	97
L106N 47+50W	.1	3	ND	15	46	53	4.31	1	33	19	93
L106N 47+75W	.1	3	ND	16	45	52	4.28	ND	36	20	94
L106N 48+00W	.1	4	ND	14	44	48	4.17	ND	33	20	88
L106N 48+25W	.1	6	ND	11	39	68	3.59	ND	26	17	66
L106N 48+50W	.2	ND	ND	11	37	70	3.52	1	26	20	61
L106N 48+75W	.1	3	ND	8	28	29	2.75	1	18	18	92
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L106N 49+00W	.2	3	ND	9	30	32	3.07	1	20	17	96
L106N 49+25W	.1	3	ND	11	31	36	3.10	1	25	13	101
L106N 49+50W	.1	3	ND	11	37	34	3.52	1	27	13	126
L106N 49+75W	.2	3	ND	12	32	45	3.18	1	21	13	153
L106N 50+00W	.2	ND	ND	13	35	51	3.43	1	24	14	153
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L94N 55+50W	.3	10	30	12	29	195	4.26	2	17	20	68
L94N 55+75W	.1	7	30	15	31	656	4.45	1	20	18	71
L94N 56+00W	.4	7	95	6	17	105	3.16	1	8	17	48
L94N 56+25W	.2	11	20	14	27	236	4.21	2	20	21	74
L94N 56+75W	.4	5	5	16	28	166	3.26	3	16	21	104
L94N 57+00W	ND	5	20	8	23	50	3.16	ND	11	16	108
L96N 50+25W	.2	8	10	10	28	160	3.45	1	18	16	69
L96N 50+50W	ND	5	5	9	32	187	3.69	1	21	19	82
L96N 50+75W	.1	6	15	11	24	131	3.35	1	15	17	85
L96N 51+00W	.7	10	10	9	23	82	2.86	1	15	19	88
L96N 51+25W	.5	6	25	9	27	70	3.40	1	16	17	82
L96N 51+50W	.5	8	20	8	28	97	2.82	1	15	17	60
L96N 51+75W	.2	6	5	9	30	457	2.85	4	17	18	53
L96N 52+50W	.4	7	20	10	29	107	3.00	1	22	17	71
L96N 52+75W	.4	6	10	14	34	118	3.21	1	20	18	50
L96N 53+00W	.4	6	10	10	33	122	3.41	2	20	18	80
L96N 53+25W	.1	6	30	13	32	539	3.65	5	23	15	111
L96N 53+50W	.1	7	35	12	39	365	3.60	2	29	18	68
L96N 53+75W	ND	ND	5	15	42	3550	3.54	3	35	21	101
L96N 54+00W	.1	6	5	15	39	206	3.34	1	34	19	86
L96N 54+25W	.7	7	5	7	28	44	2.53	1	21	17	54
L96N 54+50W	.2	3	5	13	41	2864	3.05	1	32	20	118
L96N 54+75W	.4	4	20	9	29	106	2.94	1	20	16	67
L96N 55+00W	.4	7	20	12	36	260	3.09	2	31	19	64
L96N 55+25W	.7	5	30	12	36	299	2.45	1	30	19	98
L96N 55+50W	.4	6	10	7	29	135	2.79	2	20	20	60
L96N 55+75W	.7	6	220	9	24	354	3.21	1	14	16	78
L96N 56+00W	1.0	4	220	9	24	489	2.85	1	14	19	66
L96N 56+25W	.4	7	35	9	22	171	2.99	1	13	15	57
L96N 56+50W	.6	7	30	8	19	156	2.65	1	11	16	64
L96N 56+75W	.5	6	55	6	18	64	2.51	1	6	14	52
L96N 57+00W	.5	6	20	8	21	198	2.85	1	13	15	67
L98N 36+0W	.2	4	ND	9	30	20	2.32	ND	16	12	52
L98N 36+25W	.4	5	ND	10	28	18	2.15	ND	15	14	52
L98N 36+50W	.4	6	ND	9	31	20	2.29	ND	18	13	48
L98N 36+75W	.5	4	ND	8	31	21	2.40	ND	16	15	47
L98N 37+00W	.3	7	ND	14	39	65	2.89	ND	27	15	50
L98N 37+25W	.1	5	ND	13	39	65	2.85	ND	28	14	52
L98N 37+50W	.3	5	10	13	42	112	2.99	ND	41	14	59
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L98N 37+75W	ND	6	ND	8	32	30	2.50	1	18	8	47
L98N 38+00W	ND	9	10	15	38	78	3.35	1	27	17	65
L98N 38+25W	.2	ND	ND	10	34	36	2.74	1	18	9	50
L98N 38+50W	.1	ND	ND	10	35	61	3.26	1	20	8	66
L98N 38+75W	.3	ND	ND	11	38	32	3.56	1	24	12	108
L98N 39+00W	.3	4	10	13	32	327	2.94	1	20	13	66
L98N 39+25W	.2	8	ND	15	33	242	3.36	2	21	14	59
L98N 39+50W	.3	7	ND	11	34	73	2.94	1	19	11	52
L98N 39+75W	.3	4	5	12	37	34	3.19	1	20	11	53
L98N 40+00W	.1	5	ND	9	25	15	2.37	ND	21	11	86
L98N 40+25W	.3	ND	ND	12	37	29	3.13	1	22	13	61
L98N 40+50W	.2	4	10	19	34	67	3.06	1	21	14	108
L98N 40+75W	.1	4	ND	11	34	42	3.00	1	24	13	80
L98N 41+00W	.4	7	ND	7	27	16	2.39	ND	12	10	81
L98N 41+25W	.3	4	ND	11	32	20	3.22	1	18	13	97
L98N 41+50W	.2	5	ND	15	41	52	3.83	1	37	17	70
L98N 41+75W	.4	8	ND	14	48	222	3.52	1	36	18	161
L98N 42+00W	.6	6	ND	18	37	209	2.89	2	26	20	167
L98N 42+25W	.5	7	ND	18	43	88	3.63	1	35	16	139
L98N 42+50W	.3	4	ND	9	28	66	2.59	1	15	10	124
L98N 42+75W	.4	ND	ND	14	34	55	3.36	1	27	15	176
L98N 43+00W	.2	3	ND	9	35	49	3.31	1	23	18	124
L98N 43+25W	.3	5	ND	9	33	50	2.74	1	19	13	148
L98N 43+50W	.4	6	ND	12	32	75	2.75	3	19	15	322
L98N 43+75W	.2	ND	ND	12	37	42	3.30	1	25	18	132
L98N 44+00W	.2	ND	5	13	38	65	3.60	1	26	16	80
L98N 44+25W	.3	9	5	14	36	64	3.26	3	25	16	189
L98N 44+50W	.3	3	ND	8	33	39	3.09	3	18	15	175
L98N 44+75W	.3	9	ND	17	32	82	4.23	4	26	17	469
L98N 45+00W	.6	6	ND	10	25	23	2.74	1	15	14	326
L98N 45+25W	.7	5	5	11	33	40	3.31	1	28	17	287
L98N 45+50W	.4	11	5	19	34	149	3.65	3	30	25	473
L98N 45+75W	.5	8	5	8	22	51	2.90	3	13	28	265
L98N 46+00W	.1	8	ND	15	45	127	4.01	1	39	19	166
L98N 46+25W	.6	7	ND	8	30	28	2.86	1	17	14	128
L98N 46+50W	.4	8	ND	9	32	33	2.91	1	20	14	90
L98N 46+75W	.1	8	5	10	33	38	3.15	1	23	16	92
L98N 47+00W	.7	6	ND	9	32	35	3.05	1	21	16	143
L98N 47+25W	.3	10	ND	8	29	23	2.77	1	19	16	107
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L98N 47+50W	.1	ND	ND	9	27	42	3.23	2	20	15	151
L98N 47+75W	.1	8	5	12	24	84	3.17	2	20	16	201
L98N 48+00W	.1	ND	ND	6	23	24	2.45	2	12	8	91
L98N 48+25W	.1	ND	20	9	28	30	2.76	2	19	10	166
L98N 48+50W	.1	3	10	9	32	66	2.61	1	22	10	62
L98N 48+75W	.2	6	5	9	26	67	2.54	1	20	12	71
L98N 49+00W	.1	3	ND	9	29	59	3.11	1	20	12	75
L98N 49+25W	.1	5	ND	9	26	56	2.78	1	15	10	56
L98N 49+50W	.1	5	10	9	25	64	2.48	2	13	9	43
L98N 49+75W	.2	3	ND	10	28	139	2.97	2	13	13	58
L98N 50+00W	.1	6	25	12	33	244	3.56	2	26	20	73
L98N 50+25W	.1	3	10	6	22	48	2.81	1	12	11	51
L98N 50+50W	.1	ND	25	13	26	175	3.18	1	19	14	87
L98N 50+75W	.2	3	10	7	24	44	2.70	1	12	12	56
L98N 51+00W	.2	ND	10	8	26	42	3.07	2	16	13	89
L98N 51+25W	.2	ND	ND	5	19	33	1.92	1	8	9	51
L98N 51+50W	.1	ND	20	21	49	1184	4.63	6	36	24	93
L98N 51+75W	.2	5	20	14	32	1423	3.08	5	21	15	62
L98N 52+00W	.2	7	ND	7	27	628	2.83	5	15	14	49
L98N 52+25W	.2	6	15	10	29	782	2.86	6	23	14	52
L98N 52+75W	.3	9	25	12	28	865	2.86	5	17	14	52
L98N 53+00W	.4	6	15	10	26	115	2.75	1	16	12	54
L98N 53+25W	.4	8	25	11	29	124	3.01	2	17	14	57
L98N 53+50W	.2	9	40	14	34	741	3.67	2	24	16	72
L98N 53+75W	.4	6	10	14	36	590	3.64	4	24	14	54
L98N 54+00W	.3	5	25	11	28	282	3.49	2	16	12	57
L98N 54+25W	.4	8	15	7	26	85	2.82	2	14	14	65
L98N 54+50W	.5	9	30	10	32	1063	3.47	2	19	18	60
L98N 54+75W	.5	10	20	11	35	975	3.32	2	23	17	83
L98N 55+00W	.3	5	35	10	29	517	3.04	1	21	14	70
L98N 55+25W	.8	9	40	10	20	345	3.78	1	11	16	88
L98N 55+50W	.5	7	30	10	32	224	3.37	2	23	18	67
L98N 55+75W	.7	7	30	10	33	232	2.89	2	22	16	69
L98N 56+00W	.3	10	45	9	33	174	3.71	2	21	16	73
L98N 56+25W	.1	7	30	10	37	239	4.01	2	28	15	91
L98N 56+50W	.4	8	40	7	44	479	3.45	2	23	17	81
L98N 56+75W	.5	11	45	7	42	495	3.43	2	23	18	78
L98N 57+00W	.3	6	105	7	24	1009	3.45	1	9	12	45
L100N 38+00W	.2	5	ND	11	39	26	3.08	1	18	11	84
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU +PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L100N 36+25W	.1	ND	ND	10	43	29	2.95	1	23	18	67
L100N 36+50W	1.3	ND	ND	13	47	32	3.37	3	27	28	81
L100N 36+75W	1.4	6	ND	7	24	21	1.83	3	19	26	34
L100N 37+00W	.8	ND	ND	10	39	21	3.16	3	27	25	90
L100N 37+25W	.1	ND	ND	12	55	56	3.55	2	33	20	55
L100N 37+50W	.3	ND	ND	12	51	53	3.47	2	28	20	55
L100N 37+75W	.1	ND	5	17	38	72	4.08	2	29	19	75
L100N 38+00W	.8	7	ND	19	40	73	4.25	3	30	28	78
L100N 38+25W	1.1	13	ND	20	41	75	4.24	4	31	29	81
L100N 38+50W	1.3	11	5	18	39	73	3.70	4	30	32	78
L100N 38+75W	.4	ND	ND	9	34	41	2.70	2	22	21	44
L100N 39+00W	.1	ND	ND	11	35	49	3.25	2	21	19	86
L100N 39+25W	.1	ND	5	20	33	37	4.20	1	23	20	141
L100N 39+50W	.4	ND	ND	16	58	63	4.12	2	38	21	77
L100N 39+75W	.1	ND	ND	10	41	52	3.07	1	23	17	70
L100N 40+00W	.1	ND	5	16	37	67	4.40	ND	34	9	70
L100N 40+25W	.1	ND	ND	9	31	40	3.16	ND	20	8	87
L100N 40+50W	.1	5	ND	8	30	49	2.62	1	18	20	94
L100N 40+75W	.4	ND	ND	11	37	35	3.34	2	27	20	103
L100N 41+00W	1.5	9	ND	12	39	32	3.45	3	27	32	105
L100N 41+25W	.5	ND	ND	12	37	26	3.52	2	34	22	99
L100N 41+50W	.6	ND	ND	12	37	26	3.52	1	28	22	93
L100N 41+75W	.9	4	ND	14	44	31	3.72	2	28	27	106
L100N 42+00W	1.6	7	ND	10	42	23	3.40	4	22	32	99
L100N 42+25W	.5	ND	ND	11	46	38	3.75	1	27	21	60
L100N 42+50W	.5	ND	ND	12	42	256	3.45	2	31	24	314
L100N 42+75W	.1	ND	ND	14	42	68	3.40	1	29	18	92
L100N 43+00W	.8	6	ND	14	23	78	3.50	3	19	27	123
L100N 43+25W	1.4	12	25	15	25	77	3.59	3	20	33	126
L100N 43+50W	.1	ND	ND	9	34	25	3.29	ND	26	7	388
L100N 43+75W	.1	ND	ND	9	34	31	3.32	ND	23	7	155
L100N 44+00W	.1	ND	ND	12	38	83	3.83	ND	27	14	216
L100N 44+25W	.8	ND	5	15	40	46	3.94	2	40	28	216
L100N 44+50W	.5	ND	ND	11	36	205	3.65	2	32	24	498
L100N 44+75W	.1	ND	5	10	36	224	3.62	1	33	16	517
L100N 45+00W	.1	ND	ND	9	33	204	3.34	ND	27	15	480
L100N 45+25W	.6	ND	ND	10	34	39	3.34	2	24	22	160
L100N 45+50W	.3	ND	ND	10	34	31	3.27	2	25	22	123
L100N 45+75W	.1	ND	ND	8	31	31	3.02	1	25	17	105
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CD PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L100N 46+00W	.1	4	ND	13	41	41	3.81	1	29	14	126
L100N 46+25W	.2	ND	ND	13	36	67	3.44	2	24	16	156
L100N 46+75W	.1	3	ND	10	33	36	3.15	1	18	12	145
L100N 47+00W	.2	5	ND	12	29	50	3.12	2	18	14	115
L100N 47+25W	.3	5	ND	11	28	24	2.78	4	15	11	108
L100N 47+50W	.3	4	5	13	34	37	3.34	6	25	16	271
L100N 47+75W	.1	5	ND	14	37	38	3.55	6	26	14	277
L100N 48+00W	.3	5	ND	15	44	103	3.89	3	31	16	97
L100N 48+25W	.3	ND	ND	15	42	125	3.73	4	33	23	161
L100N 48+50W	.3	7	ND	14	21	76	3.00	9	9	41	213
L100N 48+75W	.3	ND	ND	12	31	50	3.43	4	18	28	309
L100N 49+50W	.1	5	25	15	42	346	4.53	2	34	21	93
L100N 50+00W	.4	ND	ND	12	31	43	3.05	1	18	13	172
L102N 36+00W	.4	3	ND	10	40	36	2.86	1	20	10	52
L102N 36+25W	.5	4	ND	14	53	102	3.61	1	33	13	71
L102N 36+50W	.4	ND	ND	12	46	39	3.44	1	23	12	73
L102N 36+75W	.5	3	ND	10	39	40	2.75	1	24	11	52
L102N 37+00W	.3	3	ND	9	30	72	2.19	1	21	10	49
L102N 37+25W	.3	3	10	9	37	33	2.71	1	20	9	69
L102N 37+50W	.6	4	ND	13	48	209	3.39	2	27	14	79
L102N 37+75W	.5	ND	ND	13	43	121	3.28	1	30	14	89
L102N 38+00W	.5	6	30	13	50	134	3.53	1	24	17	91
L102N 38+25W	.5	4	ND	20	80	64	4.75	1	39	25	79
L102N 38+50W	.3	ND	ND	12	45	19	3.93	1	23	12	156
L102N 38+75W	.6	3	ND	15	49	32	4.05	1	28	14	113
L102N 39+00W	.5	ND	ND	13	45	27	3.57	1	25	12	64
L102N 39+25W	.5	7	ND	16	62	54	4.11	1	37	16	66
L102N 39+50W	.2	7	ND	26	91	118	5.46	2	58	16	82
L102N 39+75W	.7	5	ND	22	80	98	5.26	1	63	19	86
L102N 40+00W	.3	4	5	15	46	56	3.76	1	34	15	89
L102N 40+25W	.6	ND	ND	15	47	43	4.02	1	31	16	122
L102N 40+50W	.4	3	ND	10	42	22	3.59	1	21	14	116
L102N 40+75W	.6	6	ND	16	57	36	4.48	1	29	14	78
L102N 41+25W	.6	6	ND	14	47	54	3.95	1	31	16	88
L102N 41+50W	.6	4	ND	11	39	47	3.43	1	23	15	96
L102N 41+75W	.5	ND	ND	11	39	24	3.34	1	17	13	114
L102N 42+00W	.7	4	ND	14	45	40	3.76	1	24	18	233
L102N 42+25W	.8	4	ND	12	37	27	3.31	1	14	13	96
L102N 42+50W	.5	ND	ND	16	41	90	3.85	3	26	17	207
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L102N 42+75W	.1	ND	ND	10	23	289	2.28	3	18	10	140
L102N 43+00W	.1	4	ND	15	27	253	3.23	2	23	16	259
L102N 43+25W	.6	5	5	14	39	886	3.22	3	27	22	630
L102N 43+50W	.4	6	20	20	14	102	3.06	2	8	26	269
L102N 43+75W	.1	ND	ND	4	15	14	1.77	ND	6	10	82
L102N 44+00W	.4	3	ND	7	20	33	2.50	ND	10	14	58
L102N 44+25W	.1	ND	ND	7	25	27	2.53	1	16	11	91
L102N 44+50W	.2	5	ND	8	26	64	2.66	1	18	10	95
L102N 44+75W	.2	3	ND	8	22	26	2.28	ND	15	11	124
L102N 45+00W	.5	ND	ND	4	20	18	2.51	1	8	13	55
L102N 45+25W	.3	7	ND	5	17	11	1.94	1	8	16	153
L102N 45+50W	.1	ND	ND	9	26	22	2.52	1	20	9	63
L102N 45+75W	.1	ND	5	7	25	19	2.47	ND	16	10	105
L102N 46+00W	.1	ND	ND	13	33	81	3.40	4	24	20	230
L102N 46+25W	.2	ND	ND	10	30	100	2.74	4	19	14	96
L102N 46+50W	.1	ND	ND	10	29	25	2.72	1	23	10	154
L102N 46+75W	.1	3	ND	8	27	18	2.68	1	16	10	133
L102N 47+00W	.1	4	ND	13	32	61	3.16	6	24	17	170
L102N 47+25W	.1	4	ND	10	30	85	2.95	5	19	20	102
L102N 47+50W	1.4	7	ND	18	50	554	4.51	12	48	26	209
L102N 47+75W	1.1	4	ND	17	47	350	4.16	8	50	25	227
L102N 48+00W	1.5	5	ND	16	44	695	4.03	11	44	26	253
L102N 48+25W	.2	7	5	10	25	50	2.96	3	16	12	85
L102N 48+50W	.1	5	ND	9	26	28	2.59	2	15	10	93
L102N 48+75W	.2	7	ND	10	26	53	2.59	2	15	13	153
L102N 49+00W	.3	5	ND	8	27	47	3.07	4	17	14	231
L102N 49+25W	.1	7	5	10	28	56	2.69	3	21	15	142
L102N 49+50W	.2	4	ND	13	27	37	3.20	5	21	22	138
L102N 49+75W	.2	5	ND	11	26	34	2.73	2	23	13	111
L102N 50+00W	.3	7	5	9	27	41	3.39	1	21	16	91
L104N 37+50W	.3	5	ND	10	31	33	2.84	1	21	12	133
L104N 37+75W	.3	ND	ND	10	32	30	2.92	1	22	12	133
L104N 38+00W	.5	9	ND	10	40	31	3.04	1	19	11	66
L104N 38+25W	.3	6	ND	9	30	42	2.58	ND	21	9	80
L104N 38+50W	.4	3	5	12	49	52	3.53	1	26	14	117
L104N 38+75W	.4	7	15	10	42	99	3.03	1	21	12	97
L104N 39+00W	.1	9	ND	10	34	88	2.98	1	22	13	116
L104N 39+25W	.6	7	ND	13	39	676	3.26	2	25	19	148
L104N 39+50W	.6	8	5	14	38	417	3.18	2	31	15	117
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

(L10
L10)



VANGEOCHEM LAB LIMITED

MAIN OFFICE
1521 PEMBERTON AVE.
NORTH VANCOUVER, B.C. V7P 2S3
(604) 986-5211 TELEX: 04-352578

BRANCH OFFICE
1630 PANDORA ST.
VANCOUVER, B.C. V5L 1L6
(604) 251-5656

ASSAY ANALYTICAL REPORT

=====

CLIENT: MASCOT GOLD MINES LTD.
ADDRESS: 1440 - 800 W. Pender St.
: Vancouver, B.C.
: V6C 2V6

DATE: Sept 16 1986

REPORT#: 860464 AA
JOB#: 860464

PROJECT#: 5061 - Cariboo Bell
SAMPLES ARRIVED: Sept 16 1986
REPORT COMPLETED: Sept 16 1986
ANALYSED FOR: W

INVOICE#: 860464 NA
TOTAL SAMPLES: 3
REJECTS/PULPS: 90 DAYS/1 YR
SAMPLE TYPE: 3 ROCK PULP

SAMPLES FROM: VGC file 860411
COPY SENT TO: MASCOT GOLD MINES LTD.

PREPARED FOR: MASCOT GOLD MINES LTD.

ANALYSED BY: David Chiu

SIGNED: _____

Registered Provincial Assayer

GENERAL REMARK: None



VANGEOCHEM LAB LIMITED

MAIN OFFICE
1521 PEMBERTON AVE.
NORTH VANCOUVER, B.C. V7P 2S3
(604) 986-5211 TELEX: 04-352578

BRANCH OFFICE
1630 PANDORA ST.
VANCOUVER, B.C. V5L 1L6
(604) 251-5656

*Paul
Staley*

ASSAY ANALYTICAL REPORT

=====

CLIENT: E & B EXPLORATIONS LIMITED
ADDRESS: 1440 - 800 W. Pender St.
: Vancouver, B.C.
: V6C 2V6

DATE: Sept 26 1986

REPORT#: 860479 AA
JOB#: 860479

PROJECT#: 5061 PO 5626
SAMPLES ARRIVED: Sept 22 1986
REPORT COMPLETED: Sept 26 1986
ANALYSED FOR: Pt Pd Pd

INVOICE#: 860479 NA
TOTAL SAMPLES: 17
REJECTS/PULPS: 90 DAYS/1 YR
SAMPLE TYPE: 17 PULP

Car: Leo Bell

SAMPLES FROM: See Notes
COPY SENT TO: E & B EXPLORATIONS LIMITED

PREPARED FOR: L. SALEKEN

ANALYSED BY: David Chiu

SIGNED: _____

Registered Provincial Assayer

GENERAL REMARK: Samples from several VGC files



VANGEOCHEM LAB LIMITED

MAIN OFFICE
1521 PEMBERTON AVE.
NORTH VANCOUVER, B.C. V7P 2S3
(604) 986-5211 TELEX: 04-352578

BRANCH OFFICE
1630 PANDORA ST.
VANCOUVER, B.C. V5L 1L6
(604) 251-5656

REPORT NUMBER: 860479 AA

JOB NUMBER: 860479

E & B EXPLORATIONS LIMITED

PAGE 1 OF 1

SAMPLE #		Pt	Pd	Pd
		ppm	ppm	ppm
86-MR-009	860411	<.05	<.05	--
86-MR-012	860411	<.05	<.05	--
86-MR-013	860411	<.05	<.05	--
86-MR-014	860411	<.05	<.05	--
86-MR-016	860411	<.05	.05	.07
86-MR-024	860425	<.05	<.05	--
86-MR-025	860425	<.05	<.05	--
86-MR-027	860425	<.05	<.05	--
KR-86-120	860433	<.05	<.05	--
KR-86-121	860433	<.05	<.05	--
KR-86-122	860433	<.05	<.05	--
KR-86-129	860433	<.05	<.05	--
86-MR-028	860433	<.05	<.05	--
86-MR-037	860440	<.05	<.05	--
86-MR-038	860440	<.05	<.05	--
86-MR-039	860440	<.05	<.05	--
86-MR-042	860440	<.05	.85	.90

DETECTION LIMIT

1 Troy oz/short ton = 34.28 ppm

.05

1 ppm = 0.0001%

.05

ppm = parts per million

.05

(= less than

signed: _____

Paul Sterling

ANALYTICAL LABORATORIES LTD.
852 E. HASTINGS ST. VANCOUVER B.C. V6A 1R6
PHONE 253-3158 DATA LINE 251-1011

DATE RECEIVED: OCT 21 1986

DATE REPORT MAILED: *Oct 27/86*

GEOCHEMICAL ICP ANALYSIS

.500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER.
THIS LEACH IS PARTIAL FOR MN, FE, CA, P, CR, MG, BA, TI, B, AL, NA, K, W, SI, ZR, CE, SN, Y, NB AND TA. AU DETECTION LIMIT BY ICP IS 3 PPM.
- SAMPLE TYPE: SOILS -BOMESH AU# ANALYSIS BY AA FROM 10 GRAM SAMPLE.

ASSAYER: *D. Toye* DEAN TOYE. CERTIFIED B.C. ASSAYER.

E & B EXPLORATION PROJECT-5061 FILE# 86-3330 PAGE 1
C-B

SAMPLE#	Mo PPM	Cu PPM	Ag PPM	Mn PPM	Fe %	Cd PPM	V PPM	La PPM	Mg %	W PPM	Au# PPB
L117N 58+00W	4	352	.3	1483	4.70	1	151	14	1.02	1	33
L117N 57+75W	3	967	.6	2777	6.73	1	276	26	.89	1	67
L117N 57+50W	1	49	.1	588	3.72	1	92	12	.94	1	1
L117N 57+25W	2	47	.2	565	3.98	1	101	9	.87	1	1
L117N 55+25W	4	259	.2	1381	4.52	1	134	14	1.13	1	14
L117N 55+00W	3	546	.4	1183	5.18	1	143	23	1.18	1	28
L117N 54+75W	2	110	.2	405	3.23	1	83	9	.57	1	4
L117N 54+50W	1	120	.2	431	3.27	1	84	11	.59	1	3
L117N 54+25W	12	113	.3	1144	4.43	1	113	6	.88	1	22
L117N 54+00W	50	262	.5	6606	9.31	2	279	10	.63	2	9
L117N 53+75W	30	247	.3	4231	9.05	1	279	2	.76	2	8
L117N 53+50W	12	570	.6	2827	7.11	4	131	48	1.09	1	50
L117N 53+25W	2	56	.3	888	3.99	1	103	11	.62	1	3
L117N 53+00W	28	2451	1.8	2717	7.83	1	197	43	1.26	1	82
L117N 52+75W	14	926	.6	1652	4.84	1	158	15	.94	1	5
L117N 52+50W	12	1286	.7	1744	5.48	1	160	21	1.13	1	108
L117N 52+25W	5	421	.5	1104	4.83	1	126	16	1.11	1	25
L117N 52+00W	4	288	.2	984	3.82	1	110	8	.73	1	102
L117N 51+75W	2	89	.2	732	3.56	1	99	5	.57	1	3
L117N 51+50W	3	895	.5	748	4.68	1	108	14	.72	1	29
L117N 51+25W	3	484	.2	916	4.35	1	105	20	.60	1	13
L117N 51+00W	6	2054	.7	2364	5.11	1	162	15	.88	2	126
L117N 50+75W	2	538	.2	557	4.46	1	136	4	.54	1	9
L117N 50+50W	1	136	.1	705	4.25	1	115	7	.56	1	6
L117N 50+25W	2	71	.2	559	4.30	1	108	8	.81	1	1
L117N 50+00W	2	67	.2	553	4.21	1	108	10	.78	1	1
L115N 58+00W	3	47	.2	864	4.28	1	98	6	.48	1	1
L115N 57+75W	1	110	.2	662	4.52	1	111	8	.67	1	23
L115N 57+50W	2	64	.4	499	3.01	1	98	7	.16	1	1
L115N 57+25W	3	180	.4	1534	4.33	1	135	5	.55	1	138
L115N 56+75W	10	290	.5	524	6.20	1	154	9	.57	2	4
L115N 56+50W	3	114	.9	1208	3.79	1	92	10	.47	1	4
L115N 56+25W	2	85	.2	429	4.01	1	107	5	.58	1	1
L115N 56+00W	1	63	.4	541	4.00	1	100	8	.65	1	1
L115N 55+75W	5	117	1.1	706	4.59	1	117	11	.65	2	3
L115N 55+50W	3	59	.5	674	4.75	1	115	5	.81	1	2
STD C/AU-5	22	59	7.1	1003	3.96	17	63	36	.88	12	51

OCT 28 1986

E & B EXPLORATION

PROJECT-5061 FILE# 86-3330

PAGE 2

SAMPLE#	Mo PPM	Cu PPM	Ag PPM	Mn PPM	Fe %	Cd PPM	V PPM	La PPM	Mg %	W PPM	Au# PPB
L115N 55+25W	2	91	.2	664	4.76	1	131	5	1.52	1	3
L115N 55+00W	1	26	.1	1345	3.48	1	81	7	.54	1	1
L115N 54+75W	3	394	.7	1924	4.34	1	140	6	.73	1	49
L115N 54+50W	4	854	.3	430	4.32	1	106	6	.67	1	15
L115N 54+25W	8	219	.6	1504	4.85	1	139	7	.96	1	2
L115N 54+00W	1	56	.2	692	3.76	1	89	7	.62	1	26
L115N 53+75W	1	50	.1	572	3.90	1	91	8	.64	1	3
L115N 53+50W	3	164	.3	586	4.48	1	118	7	.75	1	38
L115N 53+25W	1	101	.2	547	3.57	1	89	9	.54	1	8
L115N 53+00W	1	45	.1	374	3.99	1	102	10	.53	1	1
L115N 52+75W	2	150	.1	723	4.30	1	120	11	.66	1	4
L115N 52+50W	1	50	.1	498	4.33	1	114	9	.61	1	3
L115N 52+25W	3	281	.4	345	4.04	1	110	11	.40	1	3
L115N 52+00W	2	302	.1	656	4.39	1	103	11	1.03	1	4
L115N 51+75W	3	3153	.5	1008	3.29	2	62	19	.77	1	13
L115N 51+50W	3	705	.4	1269	4.00	1	85	11	.84	1	7
L115N 51+25W	5	764	.6	1957	4.64	1	134	25	.89	1	18
L115N 51+00W	3	265	.3	568	4.28	1	101	14	.85	1	6
L115N 50+75W	2	67	.1	528	3.83	1	106	9	.55	1	5
L115N 50+50W	1	29	.1	458	3.08	1	76	7	.39	1	2
L115N 50+25W	1	30	.1	256	3.71	1	82	10	.54	1	2
L115N 50+00W	1	33	.3	496	3.58	1	80	9	.56	1	1
L113N 58+00W	1	59	.1	384	4.20	1	110	12	.77	1	5
L113N 57+75W	2	219	.5	550	4.64	1	121	6	.74	1	4
L113N 57+50W	2	223	.4	541	4.71	1	124	7	.76	1	8
L113N 57+25W	2	156	.2	590	4.76	1	133	7	.87	1	10
L113N 57+00W	1	111	.3	559	4.00	1	101	9	.65	1	4
L113N 56+75W	3	132	.3	921	4.16	1	100	9	.74	1	10
L113N 56+50W	1	49	.3	366	4.07	1	91	10	.73	1	4
L113N 56+25W	1	583	.3	476	4.21	1	98	7	.72	1	43
L113N 56+00W	2	66	.2	451	3.99	1	94	7	.62	1	9
L113N 55+75W	1	152	.4	388	4.29	1	97	9	.80	1	5
L113N 55+50W	1	89	.1	434	4.25	1	100	8	.82	1	2
L113N 55+25W	2	76	.2	414	4.12	1	97	7	.76	1	8
L113N 55+00W	1	590	.2	605	4.18	1	101	13	.77	1	5
L113N 54+75W	2	211	.4	469	3.96	1	99	11	.64	1	3
STD C/AU-S	21	58	6.8	973	3.96	17	62	35	.88	13	48

SAMPLE#	Mo PPM	Cu PPM	Ag PPM	Mn PPM	Fe %	Cd PPM	V PPM	La PPM	Hg %	W PPM	Au# PPB
L113N 54+50W	3	201	.2	599	3.97	1	105	5	.64	1	2
L113N 54+25W	1	29	.1	381	3.35	1	88	7	.38	1	1
L113N 54+00W	3	33	.2	376	3.73	1	88	6	.54	1	1
L113N 53+75W	24	263	.3	1738	4.93	1	127	6	1.25	1	50
L113N 53+50W	1	36	.2	255	2.80	1	67	5	.46	1	1
L113N 53+25W	1	35	.1	278	2.93	1	71	6	.47	1	1
L113N 53+00W	2	339	.3	586	4.28	1	106	5	.75	1	170
L113N 52+75W	1	257	.2	594	4.12	1	99	6	.72	1	21
L113N 52+50W	1	71	.2	407	3.77	1	89	5	.55	1	1
L113N 52+25W	2	418	.7	1103	4.31	1	124	6	.77	1	19
L113N 52+00W	3	170	.6	613	3.88	1	101	4	.60	1	2
L113N 51+75W	2	382	.1	355	4.33	1	109	6	.74	1	37
L113N 51+50W	3	506	.7	1004	4.36	1	151	8	.86	1	22
L113N 51+25W	2	284	.5	422	4.04	1	106	6	.69	1	350
L113N 51+00W	1	33	.3	289	3.81	1	86	5	.54	1	1
L113N 50+75W	1	26	.2	339	3.37	1	79	5	.45	1	1
L113N 50+50W	1	45	.3	317	3.91	1	95	8	.62	1	8
L113N 50+25W	2	96	.2	523	3.68	1	87	7	.72	1	1
L113N 50+00W	2	82	.3	796	3.91	1	104	6	.61	1	1
L111N 74+00W	4	354	.2	602	4.39	1	126	5	.64	1	102
L111N 73+75W	4	340	.3	608	4.29	1	124	4	.63	1	81
L111N 73+50W	3	568	.2	699	4.05	1	112	9	.79	1	99
L111N 73+25W	5	457	.4	776	4.27	1	116	5	.74	1	72
L111N 73+00W	5	436	.3	627	4.27	1	115	5	.71	1	57
L111N 72+75W	3	353	.3	384	3.31	1	89	8	.66	1	26
L111N 72+50W	3	350	.3	376	3.45	1	95	6	.63	1	21
L111N 72+25W	4	357	.2	417	4.43	1	122	5	.67	1	107
L111N 72+00W	4	643	.2	1038	4.43	1	120	8	1.05	1	65
L111N 71+75W	3	561	.2	625	4.98	1	147	3	1.04	1	79
L111N 71+50W	4	550	.1	620	4.91	1	144	3	1.03	1	181
L111N 71+25W	4	1843	1.2	1185	5.30	1	135	11	1.00	1	168
L111N 71+00W	4	1724	1.2	1078	5.12	1	129	9	1.01	1	76
L111N 70+75W	3	797	.3	793	5.15	1	150	3	1.13	1	158
L111N 70+50W	3	898	.2	920	5.52	1	159	6	1.23	2	64
L111N 70+25W	4	845	.2	830	5.47	1	159	5	1.19	1	59
L111N 70+00W	2	517	.1	611	4.40	1	114	10	.97	1	160
STD C/AU-S	21	58	6.9	984	3.97	17	62	35	.88	15	53

SAMPLE#	Mo PPM	Cu PPM	Ag PPM	Mn PPM	Fe %	Cd PPM	V PPM	La PPM	Mg %	W PPM	Au# PPB
L111N 69+75W	2	501	.1	651	4.34	1	121	6	.93	1	170
L111N 69+50W	3	468	.2	697	4.42	1	127	6	.86	1	99
L111N 69+25W	2	512	.2	655	4.47	1	124	5	.93	1	150
L111N 69+00W	3	481	.1	660	4.48	1	130	5	.86	1	126
L111N 68+75W	3	407	.1	768	4.83	1	145	2	.68	1	63
L111N 68+50W	2	98	.2	525	3.76	1	116	2	.54	1	9
L111N 68+25W	1	97	.2	555	3.78	1	117	2	.52	1	7
L111N 68+00W	2	179	.1	530	4.13	1	131	5	.52	1	32
L111N 67+75W	2	182	.1	521	4.06	1	128	4	.52	1	14
L111N 67+50W	2	329	.3	791	4.89	1	142	2	.48	1	21
L111N 67+25W	2	214	.2	523	4.87	1	135	2	.56	1	24
L111N 67+00W	2	249	.2	523	5.08	1	140	2	.62	1	26
L111N 66+75W	2	302	.3	826	4.91	1	136	2	.61	1	34
L111N 66+50W	2	483	.1	606	4.90	1	149	2	.80	1	44
L111N 66+25W	2	304	.1	519	5.44	1	152	3	.64	1	150
L111N 66+00W	2	297	.1	519	5.18	1	146	3	.64	1	139
L111N 65+75W	2	85	.3	698	3.66	1	109	4	.45	1	18
L111N 65+50W	2	83	.3	689	3.67	1	111	3	.44	1	22
L111N 65+25W	2	60	.4	587	3.03	1	96	4	.23	1	9
L111N 65+00W	3	91	.7	788	4.34	1	137	3	.40	1	21
L111N 64+75W	3	94	.7	752	4.33	1	134	4	.44	1	19
L111N 64+50W	2	373	.3	896	5.29	1	150	7	.63	1	40
L111N 64+25W	2	348	.2	1017	5.18	1	149	4	.66	1	810
L111N 64+00W	2	170	.4	471	4.27	1	126	3	.45	1	10
L111N 63+75W	2	50	.1	557	3.38	1	109	5	.14	1	14
L111N 63+50W	2	192	.2	753	4.11	1	104	5	.57	1	8
L111N 63+25W	2	182	.2	596	4.05	1	101	5	.55	1	11
L111N 63+00W	3	328	.3	753	4.79	1	133	5	.77	1	58
L111N 62+75W	2	210	.2	587	4.25	1	104	4	.61	1	19
L111N 62+50W	3	203	.2	633	4.37	1	106	6	.64	1	17
L111N 62+25W	3	524	.2	808	4.22	1	106	5	.73	1	14
L111N 62+00W	3	549	.3	677	4.26	1	107	6	.75	1	10
L111N 61+75W	3	62	.6	388	3.16	1	75	9	.47	1	10
L111N 61+50W	2	60	1.1	354	3.41	1	76	7	.52	1	1
L111N 61+25W	2	49	.4	1106	3.23	1	84	6	.37	1	3
L111N 61+00W	2	53	.5	1270	3.26	2	84	6	.38	1	3
STD C/AU-S	20	59	6.9	993	3.97	17	63	35	.88	13	49

SAMPLE#	Mo PPM	Cu PPM	Ag PPM	Mn PPM	Fe %	Cd PPM	V PPM	La PPM	Mg %	N PPM	Au# PPB
L111N 60+75W	2	24	.5	412	2.42	1	69	5	.17	1	4
L111N 60+50W	5	114	.7	765	3.61	1	80	5	.46	1	11
L111N 60+25W	4	102	.9	701	3.49	1	78	6	.42	1	7
L111N 60+00W	3	95	.6	366	3.33	1	72	6	.51	1	8
L109N 74+00W	4	206	.4	469	5.53	1	149	2	.64	1	59
L109N 73+75W	5	599	.2	770	5.20	1	149	3	1.23	1	90
L109N 73+50W	4	530	.2	711	5.26	1	139	3	1.09	1	65
L109N 73+25W	4	469	.3	714	4.75	1	131	3	.94	1	24
L109N 73+00W	4	623	.5	533	4.74	1	127	4	.89	1	40
L109N 72+75W	3	358	.4	490	4.10	1	116	4	.61	1	25
L109N 72+50W	3	345	.5	440	4.30	1	118	4	.64	1	29
L109N 72+25W	4	420	.4	436	5.10	1	128	3	.77	1	54
L109N 72+00W	3	162	.3	416	3.88	1	117	3	.47	1	41
L109N 71+75W	3	165	.2	414	3.81	1	117	4	.48	1	51
L109N 71+50W	4	294	.5	554	5.18	1	148	2	.60	1	53
L109N 71+25W	3	142	.5	523	4.18	1	120	4	.50	1	180
L109N 71+00W	3	105	.4	577	3.80	1	113	3	.38	1	29
L109N 70+75W	3	241	.8	685	4.93	1	130	2	.53	1	32
L109N 70+50W	3	229	.6	620	4.89	1	133	3	.58	1	25
L109N 70+25W	1	314	.2	457	3.99	1	113	5	.53	1	71
L109N 70+00W	2	293	.2	418	3.66	1	101	5	.50	1	64
L109N 69+75W	2	368	.3	493	4.54	1	135	3	.54	1	30
L109N 69+50W	2	347	.4	428	4.29	1	126	4	.54	1	28
L109N 69+25W	2	254	.2	400	4.04	1	119	5	.48	1	92
L109N 69+00W	2	211	.4	530	4.52	1	134	4	.43	1	142
L109N 68+75W	2	240	.4	543	4.60	1	134	3	.48	1	45
L109N 68+50W	1	192	.2	497	4.33	1	136	5	.52	1	31
L109N 68+25W	2	182	.3	558	4.34	1	136	6	.52	1	37
L109N 68+00W	1	190	.2	667	3.92	1	117	4	.49	1	22
L109N 67+75W	1	207	.1	448	3.99	1	114	5	.46	1	37
L109N 67+50W	1	126	.4	547	3.78	1	106	5	.44	1	140
L109N 67+25W	1	135	.3	489	3.79	1	106	5	.44	1	9
L109N 66+75W	2	242	.2	571	4.07	1	117	6	.50	1	33
L109N 66+50W	2	453	.2	617	4.79	1	134	6	.68	1	38
L109N 66+25W	1	320	.3	518	4.77	1	139	7	.60	1	44
L109N 66+00W	2	279	.4	493	4.64	1	137	7	.55	1	42
STD C/AU-S	21	58	6.9	980	3.97	17	62	35	.88	12	52

SAMPLE#	Mo PPM	Cu PPM	Ag PPM	Mn PPM	Fe %	Cd PPM	V PPM	La PPM	Mg %	W PPM	Au# PPB
L109N 65+75W	1	58	.3	615	3.36	1	118	6	.25	1	11
L109N 65+50W	1	83	.4	715	3.55	1	121	6	.29	1	24
L109N 65+25W	2	259	.1	600	4.48	1	145	9	.59	1	31
L109N 65+00W	3	291	.2	618	4.66	1	146	7	.65	1	28
L109N 64+75W	1	147	.1	509	4.96	1	166	3	.45	1	165
L109N 64+50W	1	114	.1	432	5.09	1	165	3	.32	1	39
L109N 64+25W	1	122	.1	330	1.46	1	48	10	.38	1	50
L109N 64+00W	1	323	.2	875	4.16	1	106	7	.72	1	38
L109N 63+75W	1	234	.1	638	5.33	1	124	8	.66	1	117
L109N 63+50W	1	107	.1	633	4.69	1	126	6	.61	1	26
L109N 63+25W	1	144	.2	749	4.29	1	110	10	.67	1	17
L109N 63+00W	1	146	.1	723	4.17	1	105	10	.71	1	21
L109N 62+75W	1	142	.2	555	4.00	1	110	8	.61	1	19
L109N 62+50W	1	200	.1	502	3.14	1	88	11	.66	1	20
L109N 62+25W	2	183	.1	486	3.02	1	83	10	.63	1	26
L109N 62+00W	2	405	.1	768	4.89	1	128	14	1.16	1	35
L109N 61+75W	1	170	.1	411	4.65	1	113	5	.56	1	17
L109N 61+50W	1	148	.1	783	3.91	1	100	6	.53	1	19
L109N 61+25W	1	150	.1	747	4.05	1	102	7	.56	1	27
L109N 61+00W	7	603	.3	957	6.24	1	157	7	.86	1	101
L109N 60+75W	8	663	.2	996	5.03	1	126	13	.93	1	65
L109N 60+50W	10	1034	.2	1133	5.51	1	128	14	1.06	1	87
L109N 60+25W	9	321	.5	618	4.82	1	125	11	.76	2	41
L109N 60+00W	10	327	.4	603	4.94	1	128	11	.77	1	62
L107N 71+00W	2	121	.3	477	3.88	1	114	7	.53	1	28
L107N 70+75W	4	357	.1	523	3.72	1	108	12	.62	1	53
L107N 70+50W	3	495	.1	646	4.17	1	113	13	.79	1	57
L107N 70+25W	3	343	.1	520	4.28	1	123	12	.68	1	92
L107N 70+00W	3	365	.2	527	4.30	1	122	11	.70	1	57
L107N 69+75W	2	428	.2	654	4.24	1	125	11	.68	1	160
L107N 69+50W	3	303	.2	550	4.41	1	135	11	.60	1	79
L107N 69+25W	3	324	.1	476	4.02	1	122	12	.59	1	113
L107N 69+00W	4	285	.3	504	4.18	1	121	8	.54	1	86
STD C/AU-S	21	57	6.9	989	3.97	17	62	37	.88	12	52

SAMPLE#	Mo PPM	Cu PPM	Ag PPM	Mn PPM	Fe %	Cd PPM	V PPM	La PPM	Mg %	N PPM	Au# PPB
L107N 68+75W	2	272	.4	427	4.10	1	120	6	.50	1	96
L107N 68+50W	2	197	.3	520	3.67	1	108	2	.43	1	99
L107N 68+25W	2	200	.2	369	4.08	1	115	6	.43	2	49
L107N 68+00W	3	503	.4	579	4.45	1	127	2	.58	1	56
L107N 67+75W	2	318	.3	874	3.82	1	111	3	.48	1	34
L107N 67+50W	2	448	.4	677	3.95	1	112	3	.51	1	57
L107N 67+25W	2	484	.3	497	4.20	1	120	4	.55	1	124
L107N 67+00W	3	892	.2	661	4.51	1	134	6	.88	1	135
L107N 66+75W	1	454	.2	855	4.36	1	139	9	.67	1	66
L107N 66+50W	2	455	.2	844	4.42	1	135	8	.80	1	62
L107N 66+25W	2	431	.1	736	4.62	1	147	8	.73	1	47
L107N 66+00W	2	474	.1	828	4.58	1	144	11	.79	1	36
L107N 65+75W	1	175	.1	592	4.25	1	134	6	.56	1	23
L107N 65+50W	1	240	.2	470	4.58	1	133	5	.56	1	55
L107N 65+25W	1	258	.2	377	4.22	1	118	7	.59	1	66
L107N 65+00W	2	274	.1	395	4.15	1	120	5	.60	1	124
L107N 64+75W	1	340	.2	427	4.70	1	129	5	.63	1	78
L107N 64+50W	2	385	.4	484	4.50	1	115	8	.60	1	124
L107N 64+25W	2	481	.3	568	4.42	1	135	9	.79	2	47
L107N 64+00W	2	464	.2	520	4.76	1	140	10	.72	1	57
L107N 63+75W	1	163	.3	399	4.76	1	127	4	.45	1	66
L107N 63+50W	2	237	.2	346	4.48	1	113	4	.55	1	39
L107N 63+25W	1	133	.2	447	4.06	1	116	6	.44	1	63
L107N 63+00W	1	145	.2	683	4.50	1	123	6	.39	1	39
L107N 62+75W	1	97	.1	369	3.42	1	111	6	.35	1	40
L107N 62+50W	1	323	.1	588	5.05	1	148	4	.96	1	41
L107N 62+25W	1	257	.1	520	5.33	1	148	3	1.02	1	28
L107N 62+00W	2	112	.2	336	3.69	1	101	8	.51	1	13
L107N 61+75W	3	731	1.0	1178	5.00	1	139	22	1.05	1	20
L107N 61+50W	2	198	.2	406	4.69	1	135	7	.82	1	22
L107N 61+25W	2	280	.2	545	4.79	1	126	6	.85	1	51
L107N 61+00W	1	430	.2	442	5.82	1	160	10	.93	1	32
L107N 60+75W	2	253	.1	620	4.87	1	125	6	.86	1	23
L107N 60+50W	3	241	.1	386	4.60	1	119	3	.69	1	29
L107N 60+25W	1	297	.3	824	5.09	1	132	6	.86	1	34
L107N 60+00W	3	228	.2	863	4.97	1	133	5	.71	2	25
STD C/AU-S	22	59	7.0	1005	3.91	17	63	34	.87	13	52

E & B EXPLORATION

PROJECT-5061 FILE# 86-3330

PAGE 8

SAMPLE#	Mo PPM	Cu PPM	Ag PPM	Mn PPM	Fe %	Cd PPM	V PPM	La PPM	Mg %	W PPM	Au† PPB
L105N 71+00W	1	66	.3	582	3.66	1	123	8	.39	1	29
L105N 70+75W	1	169	.2	577	3.87	1	126	11	.54	1	33
L105N 70+50W	2	354	.4	719	4.35	1	141	17	.76	1	72
L105N 70+25W	2	326	.2	777	4.56	1	152	13	.80	1	69
L105N 70+00W	1	164	.3	618	3.91	1	123	7	.56	1	34
L105N 69+75W	2	109	.2	563	3.53	1	114	9	.44	1	27
L105N 69+50W	2	261	.3	714	4.11	1	131	13	.66	1	44
L105N 69+25W	4	259	.2	618	4.05	1	122	13	.62	1	82
L105N 69+00W	2	165	.4	505	3.67	1	116	10	.50	1	124
L105N 68+75W	2	98	.3	687	3.36	1	108	8	.41	1	36
L105N 68+50W	1	33	.2	488	2.63	1	96	10	.19	1	42
L105N 68+00W	4	258	.2	616	4.00	1	120	11	.62	1	1080
L105N 67+75W	2	174	.3	492	3.58	1	113	10	.49	1	25
L105N 67+50W	3	797	.1	832	4.67	1	132	14	.98	1	86
L105N 67+25W	4	826	.3	819	4.79	1	135	15	1.01	1	68
L105N 67+00W	2	358	.4	599	4.13	1	127	14	.63	1	154
L105N 66+75W	1	146	.1	873	3.64	1	110	9	.36	1	51
L105N 66+50W	1	156	.2	798	3.55	1	109	8	.36	2	59
L105N 65+00W	1	611	.3	586	4.11	1	111	7	.69	1	80
L105N 64+75W	1	1137	.1	467	5.07	1	140	10	.85	1	135
L105N 64+50W	1	300	.3	678	4.35	1	129	8	.40	1	54
L105N 64+25W	1	677	.3	383	4.29	1	135	12	.67	2	83
L105N 64+00W	1	505	.1	442	4.39	1	128	10	.57	1	81
L105N 63+50W	1	584	.4	369	4.70	1	138	10	.61	1	83
L105N 63+25W	2	374	.2	665	4.69	1	130	12	.63	1	72
L105N 62+50W	2	772	.2	652	5.00	1	143	13	.63	1	116
L105N 62+25W	2	776	.4	632	4.81	1	139	14	.61	1	110
L105N 62+00W	1	448	.3	439	4.89	1	121	12	.72	1	56
L105N 61+75W	1	239	.4	307	3.91	1	98	11	.51	1	102
L105N 61+50W	1	150	.3	349	4.35	1	107	10	.42	1	74
L105N 61+25W	1	180	.3	357	4.59	1	113	9	.46	1	49
L105N 61+00W	1	424	.3	544	4.52	1	124	10	.71	1	78
L105N 60+75W	1	386	.3	483	4.38	1	115	10	.59	1	69
L105N 60+50W	1	396	.2	540	4.43	1	121	11	.68	1	120
L105N 60+25W	1	235	.2	369	4.47	1	98	12	.64	1	38
L105N 60+00W	1	204	.1	368	4.27	1	97	10	.59	1	19
STD C/AU-S	22	60	7.1	1025	3.89	18	65	40	.86	12	52

VANGEOCHEM LAB LIMITED

Paul Sterling

MAIN OFFICE: 1521 PEMBERTON AVE. N.VANCOUVER B.C. V7P 2S3 PH: (604)986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -- NOT ANALYZED, *AU= AQUA REGA/AAS

COMPANY: E & B EXPLORATIONS REPORT#: 860471PA DATE RECEIVED: 86/09/17
 ATTENTION: L.SALEKEN & M.TINDALL JOB#: 860471 DATE COMPLETED: 86/09/26
 PROJECT: 5061-CB PO#5612 INVOICE#: 860471NA COPY SENT TO: VANCOUVER OFFICE

ANALYST *W. Rames*

PAGE 1 OF 18

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L91N 35+00W	.2	ND	5	12	30	39	3.48	ND	20	13	109
L91N 35+25W	.1	ND	15	13	34	44	3.61	ND	24	12	100
L91N 35+50W	.2	5	15	8	29	17	2.76	ND	12	12	61
L91N 35+75W	.2	ND	5	32	16	32	5.14	ND	13	6	131
L91N 36+00W	.2	ND	5	14	17	28	3.76	ND	7	8	56
L91N 36+25W	.1	ND	5	11	40	44	3.73	ND	27	8	78
L91N 36+50W	.1	ND	10	11	41	41	3.57	ND	23	6	77
L91N 36+75W	.1	ND	5	9	34	26	2.89	ND	21	12	114
L91N 37+00W	.1	ND	10	9	34	30	2.93	ND	19	10	90
L91N 37+25W	.4	ND	15	10	41	26	3.45	ND	20	10	65
L91N 38+00W	.1	ND	15	16	37	858	3.75	4	23	13	96
L91N 38+25W	.1	ND	20	21	45	1376	4.30	4	31	14	90
L91N 38+75W	.2	6	5	11	27	119	2.65	1	15	13	41
L91N 39+00W	.1	7	5	12	29	106	2.86	2	16	11	43
L91N 39+25W	.1	4	10	14	40	265	3.63	2	22	12	58
L91N 39+50W	.1	ND	15	12	39	111	3.19	1	25	12	68
L91N 39+75W	.1	4	20	9	36	62	2.72	ND	19	11	59
L93N 36+00W	.1	ND	10	14	36	203	3.93	ND	24	12	90
L93N 36+25W	.1	5	5	6	32	21	2.63	1	13	11	47
L93N 36+50W	.1	6	10	7	30	18	2.53	ND	12	12	62
L93N 36+75W	.4	6	5	9	33	19	2.84	ND	24	17	75
L93N 37+00W	.2	ND	5	15	34	40	3.37	1	29	15	147
L93N 37+25W	.4	ND	5	13	33	93	3.82	3	22	18	128
L93N 37+50W	.3	5	5	9	34	54	2.93	3	16	17	86
L93N 37+75W	.2	5	5	8	32	18	2.95	2	16	16	84
L93N 38+25W	.4	ND	20	20	60	177	4.43	ND	58	16	108
L93N 38+50W	.2	10	5	10	34	23	2.90	1	15	14	67
L93N 38+75W	.4	11	5	6	27	16	2.11	1	11	16	48
L93N 39+00W	.4	9	5	8	25	20	2.45	1	13	17	52
L93N 39+25W	.4	6	5	9	31	21	3.01	ND	20	18	67
L93N 39+50W	.2	9	35	8	26	23	2.31	1	13	15	85
L93N 39+75W	.4	10	10	7	26	35	2.55	2	16	18	68
L95N 36+00W	.2	3	10	12	34	36	3.10	ND	24	16	68
L95N 36+25W	.1	4	5	9	25	14	2.55	ND	17	19	69
L95N 36+50W	.2	6	20	10	35	23	2.95	ND	20	13	55
L95N 36+75W	.2	3	15	10	36	22	3.12	ND	22	17	63
L95N 37+00W	.2	ND	15	11	37	21	3.33	ND	25	18	80
L95N 37+25W	.1	4	15	8	33	15	2.99	ND	18	16	69
L95N 37+50W	.1	17	5	9	34	23	2.92	ND	20	12	58
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CD PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L95N 37+75W	.1	ND	ND	9	26	33	2.59	ND	18	14	83
L95N 38+00W	.1	ND	ND	8	27	37	2.90	1	15	17	90
L95N 38+25W	.1	ND	ND	12	30	38	3.02	ND	23	15	72
L95N 38+50W	.1	ND	ND	6	24	27	2.68	1	12	16	67
L95N 38+75W	.1	ND	10	11	34	24	3.12	ND	26	13	121
L95N 39+00W	.1	ND	10	11	34	205	2.62	3	19	13	60
L95N 39+25W	.1	5	5	9	30	41	2.76	1	15	8	55
L95N 39+50W	.1	ND	5	15	44	50	3.33	2	23	10	110
L95N 39+75W	.1	8	5	8	27	44	2.39	2	15	8	70
L95N 40+00W	.1	6	5	9	29	70	2.64	2	17	9	68
L95N 40+25W	.1	ND	5	12	36	161	3.27	3	25	12	139
L95N 40+50W	.1	ND	5	9	33	204	2.80	4	19	9	71
L95N 40+75W	.1	ND	5	17	44	521	3.75	9	30	13	150
L95N 41+00W	.1	ND	ND	16	38	268	3.24	9	24	14	111
L95N 41+25W	.2	ND	5	17	41	310	3.68	10	27	14	130
L95N 41+50W	.1	ND	5	12	31	167	2.89	3	19	13	141
L95N 41+75W	.1	ND	5	9	37	38	3.27	ND	20	7	94
L95N 42+00W	.1	ND	ND	9	31	23	3.02	ND	20	9	95
L95N 42+25W	.1	ND	ND	7	31	24	3.13	1	19	8	134
L95N 42+50W	.1	12	ND	5	20	13	1.72	1	8	8	77
L95N 42+75W	.1	ND	10	9	35	39	3.20	ND	39	8	85
L95N 43+00W	.1	ND	5	8	28	30	2.95	1	22	4	96
L95N 43+25W	.1	ND	5	7	24	27	2.29	1	15	5	90
L95N 43+50W	.1	ND	5	6	24	19	2.34	1	15	8	88
L95N 43+75W	.1	7	5	5	23	19	2.17	1	9	9	61
L95N 44+00W	.1	6	5	6	23	19	2.10	1	9	7	83
L95N 44+25W	.1	6	20	6	25	26	2.48	1	9	9	61
L95N 44+50W	.2	6	5	5	24	14	2.16	1	12	10	84
L95N 44+75W	.1	3	5	6	26	27	2.65	1	14	11	70
L97N 36+00W	.1	ND	10	18	59	72	3.80	ND	51	10	63
L97N 36+25W	.1	ND	5	18	63	70	3.77	ND	53	10	60
L97N 36+50W	.1	ND	10	11	36	28	3.19	ND	28	10	73
L97N 36+75W	.1	ND	5	9	33	26	2.88	ND	26	10	62
L97N 37+00W	.1	ND	5	11	29	30	2.76	1	17	9	74
L97N 37+25W	.1	ND	5	9	31	18	2.79	ND	17	8	101
L97N 37+50W	.1	ND	20	11	34	22	2.98	ND	22	10	112
L97N 37+75W	.1	ND	5	9	33	27	2.77	ND	19	8	53
L97N 38+00W	.1	ND	10	9	31	30	3.35	ND	25	11	72
L97N 38+25W	.1	ND	10	11	37	58	3.21	ND	34	10	60
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CD PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L97N 38+50W	.1	ND	15	16	49	48	4.04	ND	37	11	93
L97N 38+75W	.1	ND	10	13	43	35	3.65	ND	27	11	85
L97N 39+00W	.1	9	5	10	36	33	2.97	ND	19	10	78
L97N 39+25W	.1	4	10	14	39	47	3.54	ND	23	12	62
L97N 39+50W	.1	8	10	13	37	47	3.38	ND	24	13	56
L97N 39+75W	.1	10	10	12	38	49	3.32	ND	24	14	52
L97N 40+00W	.1	7	5	13	40	49	3.42	ND	25	12	52
L97N 40+25W	.1	5	5	12	41	42	3.54	ND	25	12	60
L97N 40+50W	.1	ND	5	14	39	57	3.52	ND	27	14	87
L97N 40+75W	.1	ND	5	16	43	71	4.41	ND	32	14	109
L97N 41+00W	.1	ND	10	17	44	123	4.36	ND	35	13	99
L97N 41+25W	.1	ND	20	25	34	83	5.12	ND	35	8	109
L97N 41+50W	.3	ND	10	15	41	37	3.69	ND	24	15	229
L97N 41+75W	.5	3	10	12	36	22	3.21	ND	23	14	190
L97N 42+00W	.5	9	5	12	39	26	3.16	ND	21	16	82
L97N 42+25W	.3	ND	10	14	48	41	3.82	ND	28	12	86
L97N 42+50W	.5	ND	10	12	39	31	3.41	ND	30	13	148
L97N 42+75W	.4	6	5	11	36	39	3.23	ND	23	15	117
L97N 43+00W	.1	ND	20	18	37	158	3.85	2	29	16	254
L97N 43+25W	.5	ND	15	17	37	52	3.91	ND	30	13	209
L97N 43+50W	.2	ND	5	17	47	85	4.63	ND	48	17	114
L97N 43+75W	.5	ND	10	18	38	63	4.04	2	28	17	428
L97N 44+00W	.1	7	15	27	29	113	4.25	3	23	31	354
L97N 44+25W	.1	ND	15	15	46	80	3.99	ND	27	17	167
L97N 44+50W	.2	ND	10	16	38	62	4.25	ND	31	20	762
L97N 44+75W	.4	ND	20	17	40	88	4.09	ND	33	15	309
L88N 36+00W	.1	3	5	10	37	41	3.02	ND	23	10	78
L88N 36+25W	.1	5	5	12	39	56	3.06	ND	29	13	64
L88N 36+50W	.1	5	10	12	39	91	3.13	ND	26	11	74
L88N 36+75W	.1	ND	20	18	66	98	4.16	ND	31	13	69
L88N 37+00W	.1	7	10	12	37	39	2.86	ND	19	13	59
L88N 37+25W	.1	ND	15	33	36	415	3.86	ND	38	7	91
L88N 37+50W	.2	ND	5	15	42	128	3.53	ND	25	13	75
L88N 37+75W	.4	6	10	18	43	192	3.78	1	25	15	90
L88N 38+00W	.3	18	15	20	20	690	6.39	10	14	25	149
L88N 38+25W	.1	19	10	33	19	79	4.87	ND	21	6	88
L88N 38+50W	.1	5	5	16	47	124	3.66	1	27	13	88
L88N 38+75W	.2	ND	10	15	48	54	3.97	ND	27	14	97
L88N 39+00W	.1	6	10	15	44	102	3.80	ND	23	14	71
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L99N 39+25W	.1	ND	5	14	42	126	3.47	1	33	6	81
L99N 39+50W	.1	ND	10	23	58	299	4.69	ND	57	10	173
L99N 39+75W	.1	ND	5	21	41	187	3.59	ND	31	6	99
L99N 40+00W	.1	16	15	22	43	157	5.51	5	26	11	74
L99N 40+25W	.1	4	15	14	42	51	3.64	ND	27	6	60
L99N 40+50W	.1	ND	5	13	40	29	3.50	ND	25	4	81
L99N 40+75W	.1	4	10	11	41	26	3.34	1	17	9	79
L99N 41+00W	.1	ND	5	9	29	27	2.88	1	18	7	88
L99N 41+25W	.1	7	5	9	29	66	2.63	1	13	7	71
L99N 41+50W	.2	5	10	13	36	40	3.27	ND	21	10	81
L99N 41+75W	.1	5	10	14	40	45	3.72	ND	30	12	65
L99N 42+00W	.1	ND	10	17	47	64	4.40	ND	37	15	81
L99N 42+25W	.2	7	5	14	39	47	3.65	ND	23	10	71
L99N 42+50W	.3	7	5	24	47	75	4.48	ND	30	17	124
L99N 42+75W	.4	ND	5	55	45	185	4.23	2	35	36	338
L99N 43+00W	.8	8	5	16	33	53	3.29	2	16	19	132
L99N 43+25W	.6	4	5	21	33	80	3.45	2	21	29	209
L99N 43+50W	.8	ND	5	16	44	125	4.82	3	31	28	378
L99N 43+75W	1.1	9	5	9	31	144	2.82	5	14	21	210
L99N 44+00W	.8	8	5	11	35	127	3.33	2	21	16	252
L99N 44+25W	1.1	7	5	13	42	833	3.39	5	39	23	402
L99N 44+50W	.6	6	10	10	30	89	2.88	1	24	15	165
L99N 44+75W	.6	4	15	10	30	58	3.25	1	17	18	142
L99N 45+00W	.6	ND	20	15	38	126	3.95	ND	29	22	194
L99N 45+25W	.4	ND	10	16	39	63	3.72	1	28	18	134
L99N 45+50W	.6	ND	5	13	35	33	3.40	ND	21	16	144
L99N 45+75W	.6	12	5	6	28	21	2.41	2	7	14	122
L99N 46+00W	.3	ND	10	13	37	61	3.87	1	31	16	243
L99N 46+25W	.8	6	5	10	28	24	2.86	1	15	15	139
L99N 46+50W	.4	ND	5	13	32	53	4.40	1	19	11	182
L99N 46+75W	.1	ND	10	13	35	40	3.85	ND	26	9	174
L99N 47+00W	.1	6	15	6	25	13	2.41	ND	11	4	122
L99N 47+25W	.1	5	5	11	30	70	3.22	2	16	1	130
L99N 47+50W	.1	ND	5	9	30	29	3.29	ND	14	5	209
L99N 47+75W	.1	ND	5	13	36	96	3.64	1	26	8	163
L99N 48+00W	.1	4	10	8	28	28	2.79	6	9	5	129
L99N 48+25W	.1	11	10	5	23	14	2.31	3	6	5	87
L99N 48+50W	.1	ND	10	13	36	44	3.58	1	24	14	232
L99N 48+75W	.1	5	5	9	29	15	2.95	2	12	16	122
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L99N 49+00W	.2	10	5	11	12	80	2.16	1	10	19	194
L99N 49+25W	.1	9	5	7	21	20	2.41	1	10	12	103
L99N 49+50W	.1	5	10	11	22	45	2.99	ND	17	21	215
L99N 49+75W	.1	8	5	10	26	27	2.82	1	12	15	157
L99N 50+00W(A)	.1	12	10	11	28	47	2.56	1	15	12	89
L99N 50+00W(B)	.1	8	5	8	26	43	2.68	1	15	13	65
L99N 50+25W	.1	8	5	10	27	175	2.75	1	18	15	72
L99N 50+50W	.1	5	10	10	28	511	3.00	1	17	14	62
L99N 50+75W	.1	9	10	9	26	420	2.77	1	14	13	53
L99N 51+00W	.1	10	20	5	21	71	2.45	1	9	13	49
L99N 51+25W	.1	ND	115	24	35	942	5.30	6	28	18	103
L99N 51+50W	.1	5	20	8	24	101	3.09	1	11	12	74
L99N 51+75W	.2	10	50	5	17	83	2.87	2	6	12	41
L99N 52+00W	.1	5	55	10	21	418	3.84	3	12	13	66
L99N 52+25W	.1	ND	25	16	33	1225	3.62	ND	24	17	57
L99N 52+50W	.1	4	30	10	27	378	3.04	1	18	16	66
L99N 52+75W	.1	ND	15	12	28	354	3.17	1	21	13	61
L99N 53+00W	.1	ND	65	13	9	439	5.67	2	6	8	103
L99N 53+25W	.1	ND	45	12	31	141	3.67	ND	25	15	82
L99N 53+50W	.1	5	20	11	30	240	3.41	2	19	13	59
L99N 53+75W	.1	7	10	10	24	253	2.83	2	23	12	88
L99N 54+00W	.1	ND	25	14	29	308	3.65	3	26	15	85
L99N 54+25W	.1	ND	205	16	24	1318	4.89	ND	19	16	79
L99N 54+50W	.1	ND	135	15	30	1733	6.07	ND	23	14	75
L99N 54+75W	.1	6	200	11	23	653	4.55	1	11	15	61
L99N 55+00W	.1	5	70	7	19	164	3.13	ND	11	12	42
L99N 55+25W	.1	ND	40	10	34	369	4.09	ND	25	14	64
L99N 55+50W	.1	ND	360	13	12	629	5.77	ND	9	12	69
L99N 55+75W	.1	ND	760	15	21	7697	7.15	1	13	14	39
L99N 56+00W	.6	ND	165	10	19	463	3.87	ND	13	17	65
L99N 56+25W	.1	ND	145	11	25	419	3.87	ND	18	14	64
L99N 56+50W	.4	ND	810	10	22	803	6.17	ND	13	12	58
L99N 56+75W	.1	3	30	13	30	3483	3.34	1	19	13	54
L99N 57+00W	.1	ND	30	13	36	1342	3.57	ND	38	15	71
L101N 36+25W	.2	5	5	14	49	126	3.42	ND	30	12	70
L101N 36+50W	.1	4	20	15	59	62	3.80	ND	29	14	61
L101N 36+75W	.1	7	10	11	33	43	2.66	ND	19	12	52
L101N 37+00W	.4	ND	15	16	40	256	2.93	ND	36	15	66
L101N 37+25W	.2	14	5	7	27	90	1.83	1	18	12	49
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L101N 37+50W	.1	ND	5	12	37	96	2.94	1	20	12	80
L101N 37+75W	.1	ND	5	12	36	97	2.96	1	21	13	81
L101N 38+00W	.1	4	30	12	38	41	3.27	1	25	11	137
L101N 38+25W	.1	ND	5	12	37	59	2.73	1	20	13	64
L101N 38+50W	.1	3	5	11	32	27	2.87	1	18	11	86
L101N 38+75W	.1	3	10	13	37	81	3.06	1	24	13	66
L101N 39+00W	.1	7	10	15	43	83	3.71	2	24	13	60
L101N 39+25W	.1	23	50	31	20	270	6.08	10	14	14	73
L101N 39+50W	.1	5	5	10	33	26	2.82	1	22	10	56
L101N 39+75W	.1	7	5	10	36	41	2.97	1	19	12	54
L101N 40+00W	.3	8	5	7	25	21	2.17	2	11	16	59
L101N 40+25W	.1	ND	10	12	35	42	3.42	ND	26	8	150
L101N 40+50W	.1	ND	10	13	36	46	3.50	ND	28	10	139
L101N 40+75W	.2	ND	5	19	35	106	3.95	1	28	10	124
L101N 41+00W	.1	8	5	7	27	14	2.24	1	13	13	80
L101N 41+25W	.1	ND	5	10	33	20	3.00	ND	19	10	73
L101N 41+50W	.3	43	40	50	24	2806	7.90	10	20	24	97
L101N 41+75W	.1	ND	10	16	45	92	3.94	ND	37	13	65
L101N 42+00W	.7	ND	30	15	42	817	3.14	2	35	13	349
L101N 42+25W	.2	5	10	11	30	35	2.76	1	18	11	85
L101N 42+50W	.3	11	10	10	33	24	2.89	2	24	14	97
L101N 42+75W	.4	6	10	9	26	28	2.43	2	14	16	65
L101N 43+00W	.1	ND	10	12	32	41	3.00	1	28	12	53
L101N 43+25W	.3	3	5	10	32	25	2.82	1	17	12	92
L101N 43+50W	.3	ND	5	19	34	128	3.78	2	22	24	315
L101N 43+75W	.4	5	5	11	32	25	2.92	1	18	15	177
L101N 44+00W	.5	12	5	8	26	13	2.26	2	11	17	151
L101N 44+25W	.5	3	5	13	32	191	3.12	4	19	19	358
L101N 44+50W	.2	6	5	11	27	24	2.66	2	18	12	289
L101N 44+75W	.4	8	10	11	33	51	2.98	1	21	14	62
L101N 45+00W	.2	5	5	13	36	48	3.45	1	24	13	53
L101N 45+25W	.5	8	5	12	28	27	2.97	1	16	15	200
L101N 45+50W	.8	9	5	10	24	24	2.41	3	11	18	225
L101N 45+75W	.1	ND	5	11	35	29	3.53	ND	23	6	196
L101N 46+00W	.5	7	5	8	29	17	2.35	1	20	13	91
L101N 46+25W	.3	3	10	10	31	23	2.93	1	20	11	112
L101N 46+50W	.1	ND	10	12	35	46	3.40	1	27	8	107
L101N 46+75W	.1	ND	10	13	35	67	3.70	ND	30	5	187
L101N 47+00W	.1	3	10	9	30	64	2.98	2	16	9	132
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L101N 47+25W	.1	4	10	5	20	36	2.14	1	12	10	94
L101N 47+50W	.2	10	5	18	13	73	2.36	2	7	21	107
L101N 47+75W	.1	ND	5	10	30	47	2.97	1	24	10	119
L101N 48+00W	.1	4	5	7	23	27	2.26	1	16	10	90
L101N 48+25W	.1	4	30	8	23	32	2.36	1	15	10	100
L101N 48+50W	.2	ND	5	8	21	32	2.69	1	12	77	265
L101N 48+75W	.1	ND	5	7	19	33	2.96	1	9	30	154
L101N 49+00W	.2	7	5	4	13	25	2.00	1	4	25	80
L101N 49+25W	.1	6	10	6	24	17	2.47	3	12	11	64
L101N 49+50W	.1	ND	5	7	25	19	2.63	3	14	10	66
L101N 49+75W	.1	ND	10	10	27	31	2.85	1	17	10	79
L101N 50+00W	.1	ND	5	8	24	32	2.79	1	16	12	108
L013N 37+00W	.1	4	5	8	29	23	2.38	1	19	8	39
L013N 37+25W	.1	7	5	7	25	19	2.00	1	14	10	54
L013N 37+50W	.2	4	5	8	24	29	2.09	1	17	10	76
L013N 37+75W	.1	4	5	8	30	100	2.35	1	16	11	54
L013N 38+50W	.1	6	5	8	27	27	2.19	1	16	11	37
L013N 38+75W	.1	ND	5	8	26	57	2.35	1	16	10	46
L013N 39+00W	.1	4	5	9	28	48	2.28	1	20	10	51
L013N 39+25W	.1	ND	10	11	36	73	2.69	1	24	10	60
L013N 39+50W	.1	5	5	10	33	72	2.47	1	40	12	64
L013N 39+75W	.1	3	5	10	39	47	2.66	1	30	10	49
L103N 40+00W	.1	ND	5	11	38	45	2.78	1	27	9	60
L103N 40+25W	.1	ND	5	15	47	72	3.28	1	38	6	54
L103N 40+50W	.1	3	5	10	31	31	2.44	1	20	10	60
L103N 40+75W	.1	ND	5	12	38	52	3.09	ND	32	10	52
L103N 41+00W	.1	7	5	6	24	15	1.96	1	15	13	44
L103N 41+25W	.1	6	5	8	26	16	2.28	1	14	14	64
L103N 41+50W	.1	ND	5	11	30	28	3.12	1	17	14	102
L103N 41+75W	.5	8	5	8	23	26	2.16	1	12	16	78
L103N 42+00W	.1	7	10	8	19	26	1.94	1	10	14	91
L103N 42+25W	.1	6	5	7	24	25	2.14	1	13	13	72
L103N 42+50W	.1	4	5	8	26	26	2.36	1	16	10	66
L103N 42+75W	.1	3	5	8	26	21	2.72	1	12	15	86
L103N 43+00W	.1	4	5	9	30	24	2.52	1	15	14	72
L103N 43+25W	.1	ND	5	9	28	36	2.61	1	18	10	80
L103N 43+50W	.1	4	5	9	30	22	2.49	1	19	11	53
L103N 43+75W	.1	4	5	8	32	28	2.59	1	17	12	43
L103N 44+00W	.1	7	5	8	27	18	2.27	1	12	14	62
DETECTION LIMIT	.1	3	45	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L103N 44+25W	.1	6	5	12	41	35	3.70	ND	22	9	68
L103N 44+50W	.1	8	ND	11	42	23	3.32	1	21	9	78
L103N 44+75W	.1	ND	ND	18	35	64	4.30	ND	23	27	208
L103N 45+00W	.2	3	5	13	38	34	3.57	ND	22	18	154
L103N 45+25W	.2	ND	5	14	40	46	3.75	ND	30	17	199
L103N 45+50W	.2	10	5	9	30	20	2.66	1	15	13	90
L103N 45+75W	.8	ND	5	14	39	51	3.74	ND	25	20	182
L103N 46+00W	.1	5	5	10	32	21	3.18	1	20	12	128
L103N 46+25W	.2	ND	10	14	39	39	3.77	1	29	33	353
L103N 46+50W	.1	ND	5	13	37	26	3.54	ND	31	17	193
L103N 46+75W	.1	ND	10	14	44	44	4.01	ND	35	17	107
L103N 47+00W	.2	8	5	11	39	31	3.18	1	19	10	179
L103N 47+25W	.4	3	5	14	36	79	3.29	1	19	28	333
L103N 47+50W	.1	3	5	10	37	115	3.37	2	23	20	185
L103N 47+75W	.2	ND	5	23	44	380	4.30	2	34	56	235
L103N 48+00W	.1	3	5	11	38	63	3.62	1	20	15	108
L103N 48+25W	.1	ND	10	12	38	41	3.66	ND	25	13	140
L103N 48+50W	.1	ND	5	19	38	72	3.70	2	27	17	145
L103N 48+75W	.1	ND	10	12	36	34	3.54	ND	21	9	112
L103N 49+00W	.1	ND	5	15	43	71	4.30	2	29	18	124
L103N 49+25W	.1	ND	5	10	37	39	3.39	1	36	7	80
L103N 49+50W	.1	4	5	10	32	34	3.25	1	21	6	91
L103N 49+75W	.1	ND	15	20	45	115	5.01	1	45	17	219
L103N 50+00W	.1	ND	15	14	35	439	3.27	4	23	8	74
L105N 38+25W	.1	ND	10	16	58	371	4.05	1	39	9	131
L105N 38+50W	.1	ND	15	16	53	490	3.85	1	42	10	120
L105N 38+75W	.1	ND	10	13	45	215	3.41	ND	30	9	126
L105N 39+00W	.1	ND	10	21	69	478	5.00	ND	62	18	210
L105N 39+25W	.2	ND	10	17	56	437	4.32	ND	49	12	154
L105N 39+50W	.1	ND	5	20	70	718	5.08	2	68	16	164
L105N 39+75W	.1	6	5	12	42	156	3.25	2	27	10	107
L105N 40+00W	.1	5	5	13	47	151	3.39	2	27	13	74
L105N 40+25W	.7	ND	5	18	62	1009	4.54	1	63	17	176
L105N 40+50W	.4	ND	10	22	69	713	5.09	1	59	20	147
L105N 40+75W	.1	3	15	15	46	179	3.37	1	29	10	84
L105N 41+00W	.1	7	5	13	52	267	3.42	2	31	12	86
L105N 41+25W	.1	ND	15	21	70	363	4.91	5	45	17	96
L105N 41+50W	.1	6	5	12	38	108	3.06	2	24	9	78
L105N 41+75W	.1	6	5	15	67	94	4.05	2	29	15	72
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L105N 42+25W	.1	ND	5	20	51	188	4.28	3	39	8	104
L105N 42+50W	.1	ND	ND	19	58	96	4.37	3	43	5	77
L105N 42+75W	.1	ND	ND	19	57	172	4.21	2	39	6	111
L105N 43+00W	.1	ND	5	19	57	206	4.22	3	36	8	105
L105N 43+25W	.1	4	5	13	34	59	2.81	2	21	9	85
L105N 43+50W	.1	ND	5	15	47	51	3.86	1	27	8	95
L105N 43+75W	.1	ND	5	15	44	53	3.89	1	25	6	93
L105N 44+00W	.7	ND	10	22	56	996	4.69	3	50	13	213
L105N 44+25W	.8	ND	5	18	50	887	4.13	1	35	14	170
L105N 44+50W	.1	ND	5	11	31	52	3.18	ND	16	8	102
L105N 44+75W	.1	ND	5	14	43	41	3.56	1	23	5	62
L105N 45+00W	.1	ND	5	15	48	43	3.96	ND	26	5	72
L105N 45+25W	.1	5	25	16	45	75	3.95	ND	32	13	63
L105N 45+50W	.2	12	5	14	26	87	3.43	1	14	12	65
L105N 46+00W	1.1	19	5	19	18	227	4.24	2	11	40	153
L105N 46+25W	.2	ND	10	15	38	216	3.59	ND	29	14	160
L105N 46+50W	.1	ND	20	14	41	143	4.11	ND	30	19	137
L105N 46+75W	.1	ND	15	16	30	86	3.72	ND	20	72	287
L105N 47+00W	.4	ND	10	18	39	163	4.26	ND	33	69	358
L105N 47+25W	.1	ND	5	12	31	40	3.23	ND	23	17	145
L105N 47+50W	.1	ND	15	13	34	36	3.29	1	36	16	140
L105N 48+00W	.1	ND	5	14	38	38	4.18	ND	31	9	130
L105N 48+25W	.1	ND	5	11	34	43	3.83	ND	26	10	119
L105N 48+50W	.1	ND	25	11	41	56	3.81	ND	25	14	102
L105N 48+75W	.1	ND	10	10	33	31	3.15	1	23	10	104
L105N 49+00W	.1	8	5	9	31	22	3.20	2	21	9	114
L105N 49+25W	.1	ND	10	13	35	44	3.89	1	23	5	146
L105N 49+50W	.1	ND	10	17	37	95	4.08	2	27	11	105
L105N 49+75W	.1	5	10	7	30	19	3.19	1	20	9	84
L105N 50+00W	.1	14	5	4	16	10	1.42	2	4	12	40
L107N 39+50W	.1	12	5	12	39	535	2.92	2	20	11	67
L107N 39+75W	.2	11	5	13	47	50	3.36	1	21	10	96
L107N 40+00W	.2	9	5	10	35	28	2.93	1	20	8	88
L107N 40+25W	.1	11	5	12	42	39	3.15	1	22	9	50
L107N 40+50W	.1	7	5	14	47	364	3.51	3	32	9	95
L107N 40+75W	.1	3	10	14	45	263	3.37	3	31	5	73
L107N 41+00W	.1	ND	25	19	60	333	4.35	5	38	8	106
L107N 41+25W	.1	6	5	16	51	196	3.63	2	34	9	98
L107N 41+50W	.1	7	10	13	40	74	3.17	2	24	9	61
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PR PPM	ZN PPM
L107N 41+75W	.1	7	5	13	32	92	2.67	2	26	13	128
L107N 42+00W	.1	ND	ND	13	48	284	3.53	4	45	10	94
L107N 42+25W	.5	ND	5	17	60	381	4.45	3	62	12	134
L107N 42+50W	.3	ND	5	15	49	193	3.68	2	47	12	114
L107N 42+75W	.1	5	10	13	41	109	3.22	2	34	12	81
L107N 43+00W	.1	5	5	17	59	62	3.82	3	40	10	69
L107N 43+25W	.1	3	15	18	60	76	4.11	4	38	11	71
L107N 43+50W	.1	ND	15	20	69	104	4.40	ND	49	5	72
L107N 43+75W	.1	ND	15	22	59	135	4.53	4	43	11	81
L107N 44+00W	.1	9	10	15	50	51	3.85	1	31	11	65
L107N 44+25W	.1	ND	10	17	53	122	4.10	1	37	9	109
L107N 44+50W	.5	ND	10	17	50	232	3.94	ND	39	13	121
L107N 44+75W	.1	ND	5	15	49	135	3.61	3	33	9	77
L107N 45+00W	.1	3	5	14	39	51	3.61	1	24	15	129
L107N 45+25W	.1	4	10	13	41	42	3.53	ND	25	11	65
L107N 45+50W	.1	9	5	12	43	27	3.51	1	23	11	80
L107N 45+75W	.1	ND	10	15	59	49	4.07	ND	36	9	72
L107N 46+00W	.1	5	5	10	39	24	3.22	1	20	12	156
L107N 46+25W	.1	ND	20	16	46	423	3.72	1	26	15	399
L107N 46+50W	.1	ND	20	19	35	218	3.53	1	20	24	447
L107N 46+75W	.4	ND	35	27	43	359	3.76	ND	47	8	883
L107N 47+00W	.2	3	10	20	26	35	2.86	ND	18	18	148
L107N 47+25W	.1	ND	10	15	40	57	3.91	ND	33	12	94
L107N 47+50W	.6	4	10	17	28	61	4.16	1	14	23	119
L107N 47+75W	.5	3	10	11	32	85	4.17	ND	15	23	95
L107N 48+00W	.1	ND	5	14	49	139	4.25	ND	35	11	65
L107N 48+25W	.1	ND	5	14	40	68	3.86	ND	32	14	92
L107N 48+50W	.1	6	5	10	28	51	2.93	ND	18	15	98
L107N 48+75W	.2	6	15	12	37	47	3.34	ND	26	17	64
L107N 49+00W	.3	11	5	10	34	21	3.07	1	17	18	90
L107N 49+25W	.4	11	5	9	32	29	2.78	2	17	17	75
L107N 49+50W	.1	ND	5	13	40	56	3.68	1	28	12	84
L107N 49+75W	.3	5	5	11	34	48	3.24	1	17	17	134
L107N 50+00W	.7	11	5	11	29	29	3.03	2	12	18	148
L109N 41+50W	.1	ND	5	17	56	127	4.06	1	43	13	108
L109N 41+75W	.5	ND	10	22	78	362	5.37	2	78	14	148
L109N 42+00W	.3	ND	10	19	77	537	4.80	3	76	10	142
L109N 42+25W	.2	ND	10	16	55	132	3.85	3	44	13	114
L109N 42+50W	.3	ND	10	16	56	280	3.64	4	66	10	125
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L109N 42+75W	.1	ND	5	12	44	95	3.33	2	31	8	71
L109N 43+00W	.1	6	5	14	44	48	3.38	2	25	9	73
L109N 43+50W	.1	6	10	13	40	62	3.14	4	28	11	87
L109N 43+75W	.1	ND	15	12	39	73	3.22	3	29	11	107
L109N 44+00W	.1	ND	10	17	55	186	4.03	6	47	9	88
L109N 44+50W	.2	4	10	15	46	183	3.68	3	32	12	79
L109N 44+75W	.1	3	5	17	48	408	3.82	3	38	10	104
L109N 45+00W	.1	4	20	20	46	285	4.21	2	43	16	93
L109N 45+25W	2.2	ND	55	21	62	3766	5.14	2	47	39	366
L109N 45+75W	.3	12	5	10	28	294	3.25	3	11	22	134
L109N 46+00W	.4	4	25	16	45	2021	3.95	2	29	45	184
L109N 46+25W	.3	6	35	18	44	1918	3.95	2	31	31	172
L109N 46+50W	.3	ND	5	13	36	135	3.62	1	25	14	170
L109N 46+75W	.1	4	5	11	34	104	3.27	1	21	14	106
L109N 47+00W	.3	3	10	10	33	37	3.07	1	24	10	129
L109N 47+25W	.2	ND	10	11	35	44	3.16	1	24	10	134
L109N 47+50W	.2	ND	10	13	33	218	3.76	1	18	13	121
L109N 47+75W	.1	ND	10	12	34	35	3.34	1	22	9	133
L109N 48+00W	.1	ND	10	11	35	39	3.29	ND	28	8	98
L109N 48+25W	.1	9	5	6	23	18	2.14	1	11	15	78
L109N 48+50W	.3	3	75	15	30	1288	3.82	1	26	25	106
L109N 48+75W	.1	5	5	10	35	66	3.17	1	20	12	60
L109N 49+00W	.1	5	30	15	36	160	3.98	ND	27	21	80
L109N 49+25W	.1	ND	10	13	41	69	3.65	ND	28	10	75
L109N 49+50W	.1	ND	20	14	36	136	3.45	ND	26	12	100
L109N 49+75W	.1	ND	10	19	47	169	4.17	ND	44	13	88
L109N 50+00W	.1	ND	65	23	15	1089	4.06	1	11	10	91
L109N 50+25W	.1	ND	5	11	39	44	3.56	1	22	10	100
L109N 50+50W	.1	4	10	10	33	43	2.86	1	20	13	91
L109N 50+75W	.2	12	5	7	18	24	1.94	2	5	17	53
L109N 51+00W	.1	4	5	9	31	33	2.82	ND	23	10	87
L109N 51+25W	.1	4	5	12	30	76	3.05	1	22	14	97
L109N 51+50W	.1	ND	10	12	31	82	3.21	ND	21	12	87
L109N 51+75W	.1	6	10	10	26	66	2.68	1	15	13	75
L109N 52+00W	.1	ND	90	15	33	119	3.71	1	22	14	82
L109N 52+25W	.1	7	10	8	26	40	2.45	1	15	14	70
L109N 52+50W	.1	6	10	10	28	63	2.80	1	16	15	84
L109N 52+75W	.1	ND	15	9	32	49	3.18	ND	19	12	92
L109N 53+00W	.1	ND	10	11	33	47	3.83	ND	27	12	145
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L109N 53+25W	.1	9	10	10	25	36	3.21	1	15	17	125
L109N 53+50W	.1	4	5	12	42	41	3.82	ND	26	10	151
L109N 53+75W	.1	ND	5	12	35	43	3.99	ND	22	12	176
L109N 54+00W	.1	7	5	11	32	46	3.34	1	21	13	143
L109N 55+25W	.2	8	10	10	32	57	3.42	1	20	10	160
L109N 54+50W	.1	7	5	12	31	77	2.90	1	18	10	88
L109N 54+75W	.5	17	5	15	12	72	3.32	4	7	11	99
L109N 55+00W	.3	13	5	7	33	40	3.38	4	14	14	137
L109N 55+75W	.5	18	10	12	30	78	3.03	9	12	16	195
L109N 56+00W	.1	5	10	12	32	122	3.25	1	27	13	192
L109N 57+00W	.1	11	10	12	27	104	3.05	1	19	13	116
L109N 57+25W	.2	9	5	10	25	47	3.07	1	14	14	127
L109N 57+50W	.4	13	5	7	23	30	2.46	ND	12	12	120
L109N 57+75W	.1	6	20	10	29	97	3.35	ND	15	12	116
L109N 58+00W	.1	12	5	10	26	102	2.79	1	16	12	105
L111N 42+50W	.1	10	5	10	30	97	2.37	2	28	8	73
L111N 43+75W	.2	5	5	14	54	45	3.62	ND	30	9	69
L111N 44+00W	.3	4	5	15	63	53	3.88	ND	30	10	55
L111N 44+50W	.2	6	5	12	47	43	3.31	ND	25	10	58
L111N 44+75W	.2	6	5	12	54	37	3.66	ND	25	9	59
L111N 45+00W	.2	8	10	12	50	47	3.28	ND	33	12	71
L111N 45+25W	.3	ND	10	17	55	129	3.54	ND	49	10	116
L111N 45+50W	.2	9	5	14	58	40	3.61	ND	29	9	73
L111N 45+75W	.2	5	5	11	46	40	3.31	ND	25	13	70
L111N 46+00W	.2	5	10	9	35	38	2.80	ND	23	12	79
L111N 46+25W	.2	ND	5	14	50	57	3.49	ND	31	13	66
L111N 46+50W	.3	6	5	11	46	41	3.16	1	16	14	64
L111N 46+75W	.2	6	5	10	40	32	3.24	ND	23	9	87
L111N 47+00W	.1	4	15	12	44	46	3.61	ND	25	11	97
L111N 47+25W	.1	7	5	13	52	61	3.62	ND	32	12	61
L111N 47+50W	.1	10	15	16	37	204	3.84	ND	25	16	77
L111N 48+00W	.1	ND	20	20	61	111	4.62	ND	49	10	82
L111N 48+50W	.3	5	10	13	53	49	3.66	ND	27	11	85
L111N 48+75W	.2	3	10	12	43	57	3.58	1	20	12	116
L111N 49+00W	.1	7	25	15	49	124	3.98	5	26	15	58
L111N 49+25W	.1	ND	15	18	57	115	4.17	ND	42	11	75
L111N 49+50W	.2	3	10	13	43	38	3.50	1	25	12	71
L111N 49+75W	.3	ND	10	17	51	96	3.92	ND	33	13	75
L111N 50+00W	.2	5	5	11	34	46	3.18	ND	21	11	61
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L111N 50+25W	.2	7	10	11	34	38	2.85	1	22	12	60
L111N 50+50W	.2	ND	15	14	47	65	3.75	1	26	13	75
L111N 50+75W	.2	7	5	10	37	33	3.28	1	23	13	72
L111N 51+00W	.2	5	5	11	38	57	3.37	1	23	11	85
L111N 51+25W	.1	ND	10	14	40	79	3.76	ND	29	14	72
L111N 51+50W	.2	3	15	16	28	180	5.49	1	14	14	149
L111N 51+75W	.2	ND	20	17	31	228	4.09	1	22	29	112
L111N 52+00W	.1	ND	20	15	33	149	3.89	1	23	28	89
L111N 52+25W	.4	4	10	11	31	61	3.25	1	18	16	73
L111N 52+50W	.2	ND	10	12	33	84	4.05	1	22	17	90
L111N 52+75W	.2	ND	5	14	33	115	4.15	1	24	16	93
L111N 53+25W	.2	ND	10	13	37	110	4.08	ND	25	16	88
L111N 53+50W	.2	11	5	8	25	38	2.88	2	13	20	75
L111N 53+75W	.3	5	5	14	31	116	3.58	1	21	18	123
L111N 54+00W	.8	ND	15	20	57	652	4.64	5	58	20	194
L111N 54+25W	.1	ND	5	16	36	193	3.47	6	33	14	233
L111N 54+50W	.1	ND	10	17	41	85	3.94	ND	46	11	148
L111N 54+75W	.1	5	10	11	30	70	3.51	4	17	16	147
L111N 55+00W	.2	ND	10	14	39	555	3.47	4	29	12	274
L111N 57+75W	.1	5	10	16	33	188	3.62	2	23	14	154
L111N 58+00W	.3	4	10	11	34	222	3.25	4	32	16	79
L113N 43+25W	.1	7	10	9	30	75	2.88	4	17	15	157
L113N 43+50W	.2	5	5	12	31	78	3.17	2	18	14	134
L113N 43+75W	.4	7	5	15	28	75	3.15	2	13	13	169
L113N 44+00W	.1	3	5	12	36	28	2.98	1	18	11	97
L113N 44+25W	.1	3	10	11	60	32	3.65	1	24	10	104
L113N 44+50W	.1	ND	10	25	70	134	4.63	ND	52	7	106
L113N 44+75W	.1	4	5	16	59	58	3.68	ND	29	9	96
L113N 45+00W	.1	4	5	12	62	37	3.75	ND	26	9	75
L113N 45+25W	.1	4	5	15	68	45	4.05	1	34	7	69
L113N 45+50W	.1	ND	5	12	60	52	3.60	ND	26	8	70
L113N 45+75W	.1	ND	10	14	72	71	3.98	ND	34	8	67
L113N 46+00W	.1	7	10	10	52	49	3.29	1	23	9	66
L113N 46+25W	.1	ND	10	15	66	116	3.90	ND	36	7	86
L113N 46+50W	.1	4	10	13	67	49	3.95	1	32	8	62
L113N 46+75W	.2	ND	10	14	69	64	4.31	1	28	9	76
L113N 47+00W	.1	ND	10	14	64	41	4.25	ND	31	9	81
L113N 47+25W	.1	6	5	11	46	57	3.31	1	21	11	131
L113N 47+50W	.2	ND	20	12	48	146	4.01	ND	21	8	132
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L113N 47+75W	.2	13	5	7	38	20	2.97	2	13	13	46
L113N 48+00W	.1	ND	5	16	60	125	4.57	ND	35	8	65
L113N 48+75W	.1	4	5	11	42	51	3.39	1	24	10	120
L113N 49+00W	.1	ND	10	14	56	121	4.38	ND	32	10	107
L113N 49+25W	.1	ND	10	15	52	89	4.31	ND	30	7	69
L113N 49+50W	.1	8	10	10	33	21	2.94	1	18	10	79
L113N 49+75W	.1	ND	20	16	44	180	4.39	ND	31	10	96
L113N 50+50W	.1	3	10	12	37	49	3.54	ND	24	9	98
L113N 50+75W	.1	ND	10	12	43	89	3.74	ND	27	10	89
L113N 51+00W	.2	7	10	9	37	62	3.43	1	17	10	87
L113N 51+25W	.2	ND	10	14	40	66	4.00	ND	31	11	116
L113N 51+50W	.1	ND	10	13	41	43	4.00	ND	28	10	109
L113N 51+75W	.1	ND	10	14	44	86	4.29	ND	29	10	86
L113N 52+00W	.4	ND	20	13	34	250	3.97	3	27	6	105
L113N 52+25W	.2	9	10	7	24	49	2.35	1	12	11	52
L113N 52+50W	.1	3	5	13	33	154	3.28	ND	24	9	74
L113N 52+75W	.1	6	20	7	29	21	2.75	ND	16	11	72
L113N 53+00W	.1	ND	20	14	41	41	3.77	ND	33	8	78
L113N 53+25W	.1	ND	10	16	46	148	4.33	ND	35	8	73
L113N 53+50W	.2	7	10	14	24	181	4.00	ND	26	9	121
L113N 53+75W	.2	7	10	7	27	27	2.60	1	16	11	67
L113N 54+00W	.1	8	10	10	29	37	2.85	1	17	12	85
L113N 54+25W	.1	4	5	11	31	36	3.25	ND	21	11	90
L113N 54+50W	.2	ND	20	14	38	54	3.99	ND	29	11	105
L113N 54+75W	.1	4	15	13	35	51	3.39	1	21	8	118
L113N 55+00W	.1	3	15	11	36	57	3.71	1	20	11	102
L113N 55+25W	.1	10	20	9	31	22	3.71	2	14	12	110
L113N 55+50W	.2	3	10	13	37	49	4.12	1	24	11	182
L113N 55+75W	.1	7	5	17	36	153	4.20	1	29	14	81
L113N 56+00W	.1	23	20	28	20	341	6.34	5	17	16	106
L113N 56+25W	.2	3	5	16	31	106	3.94	ND	25	21	178
L113N 56+50W	.1	ND	5	13	33	105	3.91	ND	28	10	124
L113N 57+25W	.2	ND	5	16	36	116	3.98	ND	31	13	157
L113N 57+50W	.1	ND	10	13	34	51	3.79	ND	28	13	135
L113N 57+75W	.4	9	5	10	26	39	3.44	1	15	15	130
L113N 58+00W	.2	ND	5	16	34	126	4.22	1	28	15	192
L115N 45+75W	.2	9	15	14	48	64	3.70	ND	25	10	67
L115N 46+00W	.6	8	20	15	69	66	4.28	ND	29	8	59
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU #PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L115N 46+25W	.3	ND	5	15	57	65	3.67	1	31	13	73
L115N 46+50W	.1	7	10	15	63	43	4.15	1	30	12	55
L115N 46+75W	.2	4	10	15	61	66	3.83	1	33	12	56
L115N 47+00W	.3	5	15	13	61	80	3.62	1	33	12	69
L115N 47+25W	.2	7	10	15	67	66	4.12	1	35	12	60
L115N 47+50W	.1	ND	5	18	49	62	4.45	ND	43	17	130
L115N 47+75W	.1	ND	15	15	61	84	3.95	1	35	11	65
L115N 48+00W	.2	12	5	8	39	27	3.11	2	14	15	61
L115N 48+25W	.1	4	10	14	26	489	3.75	1	19	14	146
L115N 48+50W	.1	ND	15	15	46	79	4.04	1	37	15	89
L115N 48+75W	.4	ND	5	12	45	123	3.62	2	22	19	125
L115N 49+00W	.1	14	15	23	17	694	5.09	3	19	22	189
L115N 49+25W	.1	ND	10	15	48	99	3.99	ND	34	12	205
L115N 49+50W	.1	11	5	20	40	268	4.57	2	27	26	150
L115N 50+00W	.1	ND	5	14	43	42	3.55	ND	32	10	122
L115N 50+25W	.1	ND	5	13	43	45	3.54	1	28	10	136
L115N 50+50W	.1	ND	5	12	38	68	3.66	ND	31	11	123
L115N 50+75W	.1	ND	10	12	27	402	3.82	2	22	22	193
L115N 51+50W	.1	ND	15	16	43	514	4.29	1	34	14	110
L115N 51+75W	.1	ND	50	20	36	1870	4.64	1	31	19	138
L115N 52+00W	.1	3	20	13	35	154	4.00	1	32	13	120
L115N 52+25W	.1	ND	5	15	46	98	4.24	ND	36	13	128
L115N 52+50W	.1	ND	10	15	44	124	4.15	ND	35	12	91
L115N 52+75W	.3	9	5	10	29	36	2.70	1	19	15	86
L115N 53+00W	.1	3	20	15	36	149	4.16	1	20	16	117
L115N 53+25W	.1	7	5	7	33	43	3.80	4	13	12	53
L115N 54+00W	.1	ND	10	16	38	59	3.74	1	27	9	131
L115N 54+25W	.1	ND	25	16	40	93	4.33	ND	27	14	126
L115N 54+50W	.1	ND	5	12	34	30	3.55	1	22	11	134
L115N 54+75W	.1	ND	5	15	40	86	3.84	1	29	10	95
L115N 55+00W	.1	ND	15	22	41	85	4.95	ND	35	12	127
L115N 55+25W	.1	ND	10	29	17	418	6.08	1	15	10	126
L115N 55+50W	4.9	18	650	64	16	14337	19.50	15	14	17	305
L115N 55+75W	.1	13	85	28	44	1674	6.05	5	26	10	143
L115N 56+00W	.1	ND	40	18	22	661	5.66	2	16	9	215
L115N 56+25W	.1	ND	15	16	21	279	4.91	2	17	9	255
L115N 56+50W	.1	9	10	11	27	106	3.33	2	17	11	140
L115N 56+75W	.1	ND	10	13	39	77	4.12	ND	28	11	136
L115N 57+00W	.1	ND	10	13	36	80	3.97	1	20	13	119
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L115N 57+25W	.4	3	15	12	28	101	3.91	1	20	12	114
L115N 57+50W	.1	ND	5	14	33	99	3.75	1	27	13	108
L115N 57+75W	.1	ND	5	15	36	160	4.42	ND	29	16	156
L115N 58+00W	.2	ND	5	15	31	109	4.12	ND	20	19	137
L117N 46+00W	.1	10	5	13	42	70	3.25	1	26	9	52
L117N 46+25W	.1	5	5	13	51	52	3.62	1	25	8	55
L117N 46+50W	.1	ND	5	15	57	35	3.85	1	23	7	131
L117N 46+75W	.3	5	5	12	40	44	3.41	1	18	8	84
L117N 47+00W	.2	7	5	11	31	43	2.86	1	18	8	70
L117N 47+25W	.2	ND	10	15	54	79	3.85	1	29	9	64
L117N 47+50W	.3	6	5	13	69	40	4.01	1	27	8	55
L117N 47+75W	.1	ND	10	15	66	36	4.23	ND	33	9	92
L117N 48+00W	.2	8	10	8	26	25	2.77	1	10	9	51
L117N 48+25W	.1	ND	5	14	68	38	4.14	1	32	8	79
L117N 48+50W	.1	ND	5	16	70	90	4.35	1	34	9	78
L117N 48+75W	.1	ND	5	17	36	171	4.00	1	21	22	83
L117N 49+00W	.1	ND	10	20	59	2551	4.69	1	43	10	93
L117N 49+25W	.3	ND	5	16	68	440	4.39	ND	42	12	69
L117N 49+50W	.2	ND	5	11	60	138	4.12	1	23	9	86
L117N 49+75W	.1	ND	30	16	54	1155	4.16	ND	28	11	136
L117N 50+00W	.3	ND	5	11	57	123	4.04	1	41	12	103
L117N 50+25W	.3	5	5	10	56	147	3.67	2	21	12	67
L117N 50+50W	.1	ND	10	15	55	158	4.42	ND	35	12	162
L117N 50+75W	.1	26	30	18	4	4537	6.69	ND	6	34	322
L117N 51+75W	.1	ND	25	19	45	886	4.87	2	36	18	127
L117N 52+00W	.1	ND	10	21	47	704	4.50	2	41	11	225
L117N 52+50W	.1	ND	20	24	69	243	5.25	ND	61	12	86
L117N 52+75W	.1	ND	15	17	46	888	4.34	2	40	6	189
L117N 53+00W	.1	4	10	12	32	69	3.40	ND	17	11	185
L117N 53+25W	.1	3	40	18	34	709	4.62	1	23	13	117
L117N 53+50W	.2	4	10	11	38	52	3.40	1	17	10	104
L117N 53+75W	.1	5	10	12	47	100	4.41	1	24	10	106
L117N 54+00W	.3	ND	10	12	45	53	3.92	1	26	8	189
L117N 54+25W	.1	ND	10	16	50	123	4.33	ND	36	10	117
L117N 54+50W	.1	ND	10	16	51	142	4.37	ND	34	10	92
L117N 54+75W	.1	ND	20	20	53	165	5.01	ND	39	21	189
L117N 55+00W	.4	ND	35	16	45	375	4.90	2	28	21	145
L117N 55+25W	.1	ND	125	24	40	918	6.34	2	38	15	193
L117N 56+00W	.1	6	20	12	23	123	4.01	1	13	11	125
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE Z	MO PPM	NI PPM	PB PPM	ZN PPM
L119N 55+25W	.1	ND	10	17	60	151	4.93	ND	41	10	95
L119N 55+50W	.1	ND	10	16	67	100	4.78	ND	47	6	102
L119N 55+75W	.1	ND	10	18	66	158	5.13	1	41	9	82
L119N 56+00W	.1	ND	10	19	54	185	4.43	1	31	9	107
L119N 56+25W	.1	ND	5	19	35	473	4.68	3	38	19	124
L119N 56+50W	.1	ND	10	15	53	238	5.51	ND	46	4	137
L119N 56+75W	.1	ND	5	12	40	145	4.10	ND	24	7	139
L119N 57+00W	.1	4	10	9	28	71	3.56	1	12	13	102
L119N 57+25W	.2	10	5	9	23	74	2.71	2	20	8	72
L119N 57+50W	.6	6	5	11	34	805	2.82	3	30	6	80
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L117N 56+25W	.4	6	5	12	27	133	4.11	1	22	13	170
L117N 56+50W	.1	7	15	11	30	100	4.67	6	14	16	121
L117N 56+75W	.1	ND	30	20	37	399	4.71	1	28	12	94
L117N 57+25W	.1	4	5	13	25	149	3.91	1	16	21	136
L117N 57+50W	.1	ND	20	18	37	400	4.87	2	27	20	145
L117N 57+75W	.7	ND	5	13	31	125	3.96	1	21	22	178
L119N 46+00W	.1	11	10	8	20	48	2.43	1	12	6	51
L119N 46+50W	.1	6	5	9	31	51	2.67	1	24	8	48
L119N 46+75W	.1	8	5	10	32	50	2.67	1	20	10	47
L119N 47+25W	.1	8	5	10	32	37	2.71	ND	19	8	52
L119N 47+50W	.3	9	5	10	35	28	2.95	1	18	12	76
L119N 47+75W	.1	ND	5	16	58	62	4.15	ND	46	7	88
L119N 48+00W	.3	8	10	9	35	31	2.69	1	14	11	71
L119N 48+25W	.3	8	10	9	34	35	2.83	1	15	11	64
L119N 48+50W	.3	ND	10	13	52	39	4.06	ND	30	10	88
L119N 48+75W	.4	7	10	13	37	79	3.85	1	23	11	66
L119N 49+00W	.3	4	20	12	61	40	4.13	1	26	10	103
L119N 49+25W	.1	ND	5	16	65	77	4.28	1	32	12	100
L119N 49+50W	.1	ND	5	19	75	106	4.70	1	42	8	84
L119N 49+75W	.1	ND	5	26	68	248	5.34	ND	51	15	120
L119N 50+00W	.1	ND	15	23	69	117	5.33	ND	60	8	74
L119N 50+25W	.1	ND	5	18	64	97	4.82	ND	42	8	76
L119N 50+50W	.1	ND	15	13	59	174	4.56	1	30	10	150
L119N 51+00W	.2	ND	90	21	54	1223	5.42	2	41	16	205
L119N 51+25W	.3	ND	40	22	58	2886	5.10	2	50	10	191
L119N 51+50W	.1	ND	10	14	62	118	4.24	2	30	8	117
L119N 52+00W	.1	ND	25	16	52	235	3.93	1	34	6	57
L119N 52+25W	.2	ND	5	14	53	100	3.78	2	26	11	126
L119N 52+50W	.1	ND	10	18	65	102	4.54	ND	46	7	96
L119N 52+75W	.1	ND	10	16	59	81	4.31	ND	38	9	173
L119N 53+00W	.1	ND	5	18	72	47	5.21	ND	42	7	160
L119N 53+25W	.8	ND	10	19	60	557	4.69	4	49	12	180
L119N 53+50W	.2	ND	10	20	62	115	4.83	ND	43	17	97
L119N 53+75W	.2	ND	15	15	55	95	4.13	1	32	10	123
L119N 54+00W	.2	ND	20	16	46	193	4.20	1	25	16	128
L119N 54+25W	.4	7	5	9	42	43	3.38	1	19	15	105
L119N 54+50W	.1	ND	10	17	56	60	4.18	ND	44	9	109
L119N 54+75W	.2	ND	10	15	67	58	4.58	ND	37	10	92
L119N 55+00W	.2	ND	5	19	63	145	4.61	ND	40	12	87
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPH	AS PPH	AU PPB	CO PPH	CR PPH	CU PPH	FE I	MO PPH	NI PPH	PB PPH	ZN PPH
L72N 44+75W	.4	5	ND	6	25	12	2.67	1	19	11	49
L72N 45+00W	.1	3	ND	6	28	18	2.32	1	19	11	47
L72N 45+25W	.2	10	ND	5	21	11	1.63	ND	17	9	38
L72N 45+50W	.2	4	ND	8	34	25	2.26	1	27	13	66
L72N 45+75W	.2	7	ND	5	22	10	1.79	1	15	9	49
L72N 46+00W	.2	6	ND	6	27	14	1.89	1	19	10	61
L72N 46+25W	.2	ND	ND	11	48	44	2.93	ND	40	19	96
L72N 46+50W	ND	4	ND	5	22	10	1.50	ND	14	9	46
L72N 46+75W	ND	ND	ND	6	30	23	2.14	1	22	9	60
L72N 47+00W	ND	3	ND	9	34	29	2.36	1	28	10	77
L72N 47+25W	ND	ND	ND	52	60	79	5.05	1	56	20	124
L72N 47+50W	.2	6	ND	6	26	12	1.80	1	15	9	40
L72N 47+75W	ND	3	ND	12	42	29	2.57	1	28	10	82
L72N 48+00W	ND	5	ND	7	27	14	1.67	ND	17	8	51
L72N 48+25W	.3	7	ND	8	36	16	1.81	ND	22	8	52
L72N 48+50W	.2	ND	ND	11	49	23	2.47	1	27	9	100
L72N 48+75W	.3	6	ND	8	25	20	2.07	ND	17	11	55
L72N 49+00W	.7	ND	ND	17	55	117	3.87	1	54	19	99
L72N 49+25W	.2	ND	ND	16	58	87	4.21	ND	61	19	126
L72N 49+50W	.3	ND	ND	13	51	80	3.45	ND	48	15	119
L72N 49+75W	ND	ND	ND	25	36	95	4.19	1	31	12	193
L72N 50+00W	ND	4	ND	8	25	19	1.69	ND	18	11	40
L74N 35+00W	.2	8	ND	5	21	9	2.06	1	14	10	60
L74N 35+25W	.5	7	ND	6	24	14	2.21	1	16	13	69
L74N 35+50W	.8	8	ND	9	33	15	1.76	1	20	13	49
L74N 35+75W	.6	8	ND	9	36	23	1.85	1	21	12	57
L74N 36+00W	.4	3	ND	10	44	22	2.28	1	29	10	53
L74N 36+25W	ND	ND	ND	13	35	28	2.76	1	28	16	80
L74N 36+50W	.3	3	10	13	39	33	2.91	1	33	15	85
L74N 36+75W	.3	5	ND	9	29	16	2.14	1	18	14	87
L74N 37+00W	.9	7	ND	6	22	12	1.65	1	14	12	32
L74N 37+25W	.6	8	ND	6	21	11	1.72	1	12	11	39
L74N 37+50W	.7	9	ND	7	24	14	1.92	1	14	13	35
L74N 37+75W	1.0	7	ND	10	29	36	2.30	1	22	15	66
L74N 38+00W	.8	9	5	15	37	212	3.25	2	30	17	76
L74N 38+25W	1.2	13	ND	14	32	141	2.89	1	29	19	65
L74N 38+75W	.6	6	ND	7	24	39	2.28	1	18	13	54
L74N 39+00W	.7	6	ND	6	21	31	1.96	1	14	12	46
L74N 39+25W	1.0	10	ND	5	19	13	1.74	1	11	14	71
DETECTION LIMIT	.1	3	.05	1	1	1	.01	1	1	2	1

VANGEOCHEM LAB LIMITED

MAIN OFFICE: 1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604)986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO₃ TO H₂O AT 95 DEG. C FOR 90 MINUTES AND IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE. ND= NOT DETECTED. - = NOT ANALYZED. +AU= GEOCHEM

COMPANY: E&B EXPLORATIONS REPORT#: 860358PA DATE RECEIVED: 86/06/06
 ATTENTION: L.SALEKEN & M.TINDALL JOB#: 860358 DATE COMPLETED: 86/08/18
 PROJECT: 5061-CB PO#5532 INVOICE#: 860358NA COPY SENT TO: VANC.OFFICE

ANALYST W. Reeves

PAGE 1 OF 6

SAMPLE NAME	AG PPM	AS PPM	AU +PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L66N 33+75W	.1	7	ND	12	30	52	2.60	1	25	14	54
L66N 30+00W	.2	ND	ND	11	34	28	2.62	ND	29	12	67
L66N 30+25W	ND	4	ND	9	35	32	2.67	ND	30	10	61
L66N 30+50W	.2	6	ND	6	22	14	1.54	ND	15	9	46
L66N 30+75W	.1	5	ND	9	27	21	2.09	1	19	9	57
L66N 31+00W	.2	ND	ND	10	28	21	2.18	ND	22	10	51
L66N 31+25W	.1	ND	ND	10	34	30	2.58	ND	29	10	72
L66N 31+50W	.2	ND	ND	7	25	15	2.05	1	17	9	54
L66N 31+75W	.4	ND	ND	13	30	24	2.37	ND	24	13	72
L66N 32+00W	.4	ND	ND	11	36	38	2.55	ND	34	10	76
L66N 32+25W	ND	ND	ND	11	34	26	2.57	ND	27	11	75
L66N 32+50W	.2	ND	ND	8	31	27	2.29	ND	27	11	66
L66N 32+75W	.2	5	ND	7	23	12	1.65	ND	16	6	74
L66N 33+00W	.4	ND	ND	8	35	41	2.22	ND	29	11	71
L66N 33+25W	.4	ND	ND	14	51	63	3.73	ND	48	16	111
L66N 33+50W	.2	3	ND	9	26	21	2.14	ND	19	9	45
L66N 33+75W	.1	ND	ND	13	46	52	3.35	ND	45	11	114
L66N 34+00W	.1	4	ND	9	34	25	2.37	ND	24	11	46
L66N 34+25W	ND	ND	ND	16	29	109	3.29	1	26	17	60
L66N 34+50W	.1	ND	ND	9	30	18	2.04	ND	22	9	51
L66N 34+75W	.1	ND	ND	9	33	19	2.01	1	29	10	38
L66N 35+00W	.2	ND	ND	8	37	32	2.14	ND	27	10	59
L66N 35+25W	.2	ND	ND	9	33	25	2.26	ND	26	11	56
L66N 35+50W	.2	ND	ND	13	47	49	3.56	1	38	12	76
L66N 35+75W	.2	ND	ND	7	33	19	2.18	ND	25	9	50
L66N 36+00W	.1	ND	ND	12	42	31	2.74	ND	29	10	76
L66N 36+25W	.2	ND	5	17	50	43	3.37	ND	37	12	60
L66N 36+50W	.6	ND	ND	21	74	106	5.96	1	62	15	170
L66N 36+75W	.1	ND	ND	10	43	28	2.61	1	31	10	75
L66N 37+00W	.4	ND	5	13	40	43	3.21	1	36	14	64
L66N 37+25W	.3	ND	5	17	44	42	3.37	1	33	13	76
L66N 37+50W	.1	3	5	11	65	25	2.89	1	27	16	64
L66N 37+75W	.2	3	5	10	31	29	2.30	1	24	17	54
L66N 38+00W	.2	6	ND	13	28	26	2.05	2	17	19	64
L66N 38+25W	.2	3	ND	8	32	16	1.82	1	17	16	55
L66N 38+50W	.5	3	ND	23	63	218	6.23	1	92	24	169
L66N 38+75W	.3	7	ND	14	44	36	2.86	1	30	19	104
L66N 39+00W	.4	ND	5	29	66	214	7.19	3	106	28	165
L66N 39+25W	.2	3	ND	14	33	48	3.14	2	25	17	69
DETECTION LIMIT	.1	3	+5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	FE PPM	ZN PPM
L66N 39+50W	.1	7	ND	4	22	11	1.72	ND	13	7	38
L66N 39+75W	.1	7	ND	6	21	20	1.71	ND	14	7	32
L66N 40+00W	.1	11	ND	13	57	69	2.99	ND	41	7	42
L66N 40+25W	.1	7	ND	6	32	32	2.41	ND	28	7	26
L66N 40+50W	.1	6	ND	6	29	30	2.22	ND	26	7	39
L66N 40+75W	.1	5	ND	11	36	58	2.95	ND	34	7	56
L66N 41+00W	.1	5	ND	6	21	21	1.74	ND	13	7	40
L66N 41+25W	.2	9	ND	6	21	16	1.89	ND	12	10	51
L66N 41+50W	.4	8	ND	7	34	20	1.96	ND	17	9	45
L66N 41+75W	.3	6	ND	7	21	27	1.66	ND	16	6	45
L66N 42+00W	.3	11	10	10	31	55	2.60	ND	26	13	52
L66N 42+25W	.4	8	ND	3	18	10	1.53	ND	9	7	35
L66N 42+50W	.2	7	ND	7	26	23	2.36	ND	20	6	61
L66N 42+75W	.4	6	ND	5	28	15	2.39	ND	14	11	76
L66N 43+00W	.3	5	ND	6	26	14	2.47	ND	13	10	59
L66N 43+25W	.1	8	ND	6	24	16	2.19	ND	13	7	61
L66N 43+50W	.2	6	ND	4	19	14	1.97	ND	10	6	50
L66N 43+75W	.1	3	ND	5	19	10	1.76	ND	11	4	68
L66N 44+00W	.1	3	ND	6	27	13	2.67	ND	16	7	109
L66N 44+25W	.1	5	ND	4	19	10	1.90	ND	10	5	63
L66N 44+50W	.1	3	ND	11	29	44	2.35	1	32	10	66
L66N 44+75W	.2	8	ND	7	24	14	2.16	ND	16	9	97
L66N 45+00W	.1	ND	ND	16	64	67	4.33	ND	57	10	106
L66N 45+25W	.4	ND	ND	22	57	104	4.20	ND	50	14	75
L66N 45+50W	.1	ND	ND	9	34	20	2.84	ND	20	9	86
L66N 45+75W	.4	3	ND	9	52	13	2.71	ND	21	7	99
L66N 46+00W	.1	4	ND	10	37	24	2.83	ND	27	7	68
L66N 46+25W	.7	8	ND	8	29	28	2.83	1	18	13	65
L66N 46+50W	.7	7	ND	13	36	56	4.00	1	27	17	111
L66N 46+75W	.1	4	ND	8	23	22	2.07	1	18	17	62
L66N 47+00W	.2	6	ND	8	27	14	2.19	1	14	17	91
L66N 47+25W	.2	4	ND	13	39	48	2.91	1	34	21	57
L66N 47+50W	.1	6	ND	7	20	17	2.12	1	14	16	81
L66N 47+75W	.1	6	5	10	22	36	2.56	1	19	21	59
L66N 48+00W	.2	6	ND	8	34	16	2.30	1	16	16	50
L66N 48+25W	.1	4	ND	6	26	18	2.28	1	12	17	43
L66N 48+50W	.1	4	ND	12	32	33	2.96	1	22	19	160
L66N 48+75W	.2	6	ND	9	25	21	2.40	2	20	21	60
L66N 49+00W	.1	7	ND	11	23	17	2.13	1	12	19	61
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L68N 49+25W	.2	8	5	5	27	14	2.16	1	10	9	47
L68N 49+50W	.3	4	5	10	30	36	2.34	1	19	12	69
L68N 49+75W	.3	8	5	10	37	36	2.56	1	26	10	48
L68N 50+00W	.2	5	5	8	23	30	2.27	1	16	15	73
L68N 30+00W	.4	ND	5	10	35	63	2.70	1	39	12	57
L68N 30+25W	.3	3	5	9	32	47	2.35	ND	30	11	56
L68N 30+50W	.4	ND	5	11	39	65	2.93	1	43	12	67
L68N 30+75W	.3	6	ND	9	29	28	2.35	ND	23	10	44
L68N 31+00W	.4	5	ND	9	26	22	2.16	1	22	11	38
L68N 31+25W	.4	7	5	11	38	39	3.02	1	29	14	48
L68N 31+50W	.4	9	10	11	32	38	2.87	1	27	14	48
L68N 31+75W	.5	5	5	10	30	28	2.42	1	23	11	71
L68N 32+00W	.4	6	10	5	25	12	2.20	1	15	10	67
L68N 32+25W	.3	5	5	6	23	15	1.69	ND	14	9	52
L68N 32+50W	.5	5	ND	7	24	22	1.91	1	20	10	59
L68N 32+75W	.4	5	ND	7	23	15	1.96	1	15	11	41
L68N 33+00W	.4	5	5	6	22	13	1.79	1	14	8	63
L68N 33+25W	.4	8	10	7	25	18	2.28	1	19	10	53
L68N 33+50W	.4	6	20	5	21	13	1.31	1	15	9	47
L68N 33+75W	.4	ND	10	6	24	24	1.57	1	25	11	64
L68N 34+00W	.4	ND	20	7	34	44	2.17	1	34	12	66
L68N 34+25W	.5	ND	10	9	36	46	2.61	1	36	12	67
L68N 34+50W	.7	ND	10	16	51	88	3.99	1	57	16	122
L68N 34+75W	.5	7	5	8	28	24	2.15	1	23	11	44
L68N 35+00W	.6	6	10	10	32	39	2.61	1	30	13	49
L68N 35+25W	.6	4	ND	7	25	20	1.86	1	16	12	39
L68N 35+50W	.5	6	10	7	26	26	1.98	1	20	13	46
L68N 35+75W	.5	4	10	9	25	19	1.80	1	19	11	48
L68N 36+00W	.7	ND	5	13	56	120	4.17	1	60	18	122
L68N 36+25W	.4	ND	5	10	35	56	2.88	1	32	14	73
L68N 36+50W	.5	ND	5	7	28	35	2.28	1	24	12	55
L68N 36+75W	.6	5	5	8	24	16	1.71	1	17	12	40
L68N 37+00W	.4	6	5	7	23	15	1.71	1	17	10	50
L68N 37+25W	.5	ND	5	12	36	36	2.72	1	27	13	102
L68N 37+50W	.4	3	20	10	29	27	2.21	1	20	12	64
L68N 37+75W	.5	5	ND	9	27	29	2.18	1	25	10	50
L68N 38+25W	.4	4	ND	7	24	16	1.89	ND	18	11	39
L68N 38+50W	.4	ND	ND	10	39	43	2.89	1	30	17	94
L68N 38+75W	.5	9	5	5	20	12	1.47	1	15	11	40
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MG PPM	NI PPM	FE PPM	ZN PPM
L76N 49+50W	.1	ND	ND	7	31	59	2.52	1	21	10	89
L76N 49+75W	.1	ND	5	5	19	14	1.55	ND	13	9	34
L76N 50+75W	.1	ND	ND	2	14	6	1.24	ND	5	8	23
L76N 51+00W	.1	ND	ND	5	23	16	1.99	ND	14	10	46
L76N 51+25W	.1	ND	ND	5	23	15	1.96	ND	16	11	46
L76N 51+50W	.6	ND	ND	9	44	33	2.38	ND	32	17	70
L76N 51+75W	.1	ND	ND	4	22	15	1.73	1	11	9	36
L76N 52+00W	.1	ND	ND	6	26	21	2.18	1	17	11	43
L76N 52+25W	.1	ND	ND	6	25	16	2.19	1	16	13	60
L76N 52+50W	.1	3	ND	5	22	22	1.72	1	16	10	45
L76N 52+75W	.1	ND	ND	7	32	20	2.41	1	18	10	56
L76N 53+00W	.1	ND	5	8	31	21	2.47	ND	22	10	60
L76N 53+25W	.2	ND	ND	9	33	18	2.28	1	21	11	75
L76N 53+75W	.2	ND	10	21	28	46	3.67	ND	20	9	124
L76N 54+00W	.4	3	10	20	26	39	3.58	1	16	10	127
L76N 54+25W	.4	4	5	5	16	9	1.59	ND	7	10	44
L76N 54+50W	.3	3	ND	7	23	18	2.02	1	12	12	37
DETECTION LIMIT	.1	3	45	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	FE PPM	ZN PPM
L68N 39+00W	.3	6	ND	13	44	45	3.23	1	37	15	105
L68N 39+25W	.2	ND	ND	19	46	46	3.30	1	36	16	102
L68N 39+50W	.1	3	ND	11	39	27	3.02	ND	29	12	95
L68N 39+75W	.1	ND	ND	13	39	25	3.00	ND	29	13	66
L68N 40+00W	.2	3	ND	10	45	60	2.94	1	34	10	64
L68N 40+25W	.3	5	ND	10	45	66	2.90	1	34	13	64
L68N 40+75W	.1	6	ND	5	23	13	1.87	1	12	8	62
L68N 41+00W	.1	3	ND	10	40	30	3.41	1	27	14	91
L68N 41+25W	.1	8	ND	5	27	20	1.77	1	15	13	40
L68N 41+50W	.4	7	ND	6	29	15	2.46	1	16	13	58
L68N 41+75W	.1	ND	ND	8	37	20	2.81	ND	23	11	88
L68N 42+00W	.1	4	ND	8	33	24	2.80	1	24	10	56
L68N 42+25W	.2	ND	ND	13	68	30	3.44	1	36	9	94
L68N 42+50W	.4	3	ND	12	60	21	3.19	1	33	11	98
L68N 42+75W	.4	5	ND	11	59	17	3.42	1	23	13	118
L68N 43+00W	.3	3	ND	9	43	19	2.93	1	23	10	102
L68N 43+25W	.2	5	ND	9	47	29	3.24	1	26	10	93
L68N 43+50W	.4	4	ND	6	25	52	1.40	1	25	8	39
L68N 43+75W	.3	ND	ND	13	44	56	3.10	1	35	14	75
L68N 44+00W	.2	6	ND	6	28	18	2.27	1	17	12	53
L68N 44+25W	.4	ND	ND	21	67	102	4.56	1	64	23	116
L68N 44+50W	.4	3	ND	7	33	17	2.84	1	15	14	95
L68N 44+75W	.3	6	ND	6	28	15	2.37	1	15	8	77
L68N 45+50W	.4	4	ND	15	44	76	3.29	1	30	15	59
L68N 45+75W	.3	5	ND	11	34	46	2.54	1	26	13	57
L68N 46+00W	.4	3	ND	8	33	21	2.85	1	19	13	74
L68N 46+25W	.4	ND	ND	10	41	22	3.26	1	26	13	71
L68N 46+50W	.3	4	ND	6	25	14	1.94	1	14	11	38
L68N 46+75W	.4	4	10	6	26	24	1.74	1	16	12	28
L68N 47+25W	.1	7	ND	5	23	14	1.94	1	10	10	29
L68N 47+50W	.3	9	ND	6	26	11	1.93	1	13	10	44
L68N 47+75W	.4	5	ND	10	32	31	2.53	1	23	15	55
L68N 48+00W	.3	4	ND	7	31	14	2.25	1	17	10	71
L68N 48+25W	.2	ND	ND	14	39	46	3.20	ND	32	14	148
L68N 48+50W	.4	4	ND	8	37	16	2.17	1	17	9	54
L68N 48+75W	.2	ND	ND	10	35	31	3.16	1	26	13	88
L68N 49+00W	.1	ND	5	10	32	20	2.69	ND	22	11	220
L68N 49+25W	.3	ND	ND	11	38	32	3.05	1	28	14	75
L68N 49+50W	.1	3	ND	8	31	20	2.64	1	18	13	67
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU +PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	FE PPM	ZN PPM
L68N 49+75W	.1	5	ND	8	28	28	2.66	ND	19	10	57
L68N 50+00W	.1	5	ND	9	28	26	2.44	1	14	13	46
70N 30+00W	.2	ND	ND	14	48	51	3.73	ND	37	18	131
70N 30+25W	.2	ND	ND	14	50	68	3.71	ND	41	18	90
70N 30+50W	.1	ND	ND	12	40	43	2.92	ND	27	11	71
70N 30+75W	.2	ND	ND	13	36	30	2.99	ND	25	11	95
70N 31+00W	.2	3	ND	11	39	27	2.68	ND	24	19	73
70N 31+25W	.1	4	ND	10	31	27	2.44	ND	21	12	54
70N 31+50W	.1	ND	ND	12	36	37	2.81	ND	25	13	64
70N 31+75W	.2	3	ND	7	25	17	1.96	1	15	10	45
70N 32+00W	.1	3	ND	9	26	19	2.11	ND	14	11	51
70N 32+25W	.2	6	ND	7	25	13	2.03	ND	13	9	73
70N 32+50W	.2	3	ND	6	26	14	2.27	ND	12	9	43
70N 33+00W	.1	4	ND	13	36	94	3.39	ND	31	13	70
70N 33+25W	.2	7	ND	9	28	32	2.28	ND	19	11	34
70N 33+50W	.3	7	ND	8	28	16	2.34	ND	19	11	56
70N 33+75W	.2	5	ND	9	31	20	2.62	ND	21	14	66
70N 34+00W	.1	3	ND	11	35	38	3.09	ND	28	14	69
70N 34+25W	.2	7	ND	7	24	22	1.84	1	15	10	36
70N 34+50W	.1	6	ND	9	23	20	1.85	ND	16	8	35
70N 34+75W	.2	3	ND	9	33	22	2.65	ND	28	12	67
70N 35+00W	.3	6	ND	6	28	18	2.32	ND	19	14	57
70N 35+25W	.3	5	ND	9	34	26	2.42	1	23	13	46
70N 35+50W	.3	4	ND	11	40	36	2.81	ND	30	13	64
70N 35+75W	.3	8	ND	6	24	14	1.67	ND	16	11	38
70N 36+00W	.3	8	ND	6	25	13	1.73	ND	15	11	36
70N 36+25W	.4	9	ND	13	37	24	3.44	1	22	15	56
70N 36+50W	.2	6	ND	10	35	24	2.16	1	19	13	61
70N 36+75W	.1	8	ND	9	26	22	1.87	ND	16	11	52
70N 37+00W	.2	12	ND	6	24	15	1.75	1	12	12	43
70N 37+25W	.2	ND	ND	18	51	53	3.70	2	37	18	114
70N 37+50W	.3	4	ND	11	37	29	2.59	1	27	14	79
70N 37+75W	.5	10	ND	7	27	14	1.98	ND	18	12	37
70N 38+00W	.2	6	ND	8	30	21	2.22	1	17	12	60
70N 38+25W	.3	9	5	8	30	17	2.29	ND	17	11	83
70N 38+50W	.2	7	ND	9	33	17	2.38	ND	18	12	88
70N 38+75W	.1	8	ND	8	38	27	2.73	ND	21	14	68
70N 39+00W	.3	11	ND	5	27	14	1.63	ND	18	12	49
70N 39+25W	.4	13	ND	5	24	13	1.83	1	14	12	50
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	FE PPM	ZN PPM
70N 39+50W	.1	6	ND	6	25	16	1.98	1	16	12	47
70N 39+75W	.3	7	ND	5	22	10	1.61	1	14	10	45
70N 40+50W	.3	4	ND	12	32	27	2.12	1	22	13	64
70N 40+75W	.5	ND	ND	8	31	22	2.19	1	20	12	65
70N 41+00W	.5	ND	ND	9	39	52	2.66	1	30	14	65
70N 41+25W	.2	5	ND	5	26	13	1.90	1	16	9	45
70N 41+50W	.2	5	ND	5	24	15	1.90	ND	16	10	40
70N 42+00W	.1	3	ND	5	24	14	1.59	ND	19	10	44
70N 42+50W	.1	4	ND	6	28	18	2.37	ND	16	9	46
70N 42+75W	.1	ND	5	6	28	17	2.44	ND	17	9	62
70N 43+00W	.1	3	ND	7	33	29	2.16	1	23	11	46
70N 43+25W	.3	4	ND	5	27	14	1.69	1	13	10	50
70N 43+50W	.1	4	5	8	34	23	2.96	ND	25	11	76
70N 43+75W	.1	ND	ND	8	33	24	3.01	ND	24	9	76
70N 44+00W	.2	5	5	8	32	23	2.75	ND	23	9	68
70N 44+25W	.3	3	ND	7	44	14	2.66	ND	16	10	87
70N 44+50W	.3	ND	ND	8	36	25	2.50	1	24	11	46
70N 44+75W	.1	4	5	10	38	32	2.78	1	22	12	53
70N 46+00W	.2	7	ND	6	26	18	2.29	ND	16	11	42
70N 46+25W	.2	6	ND	10	31	27	2.52	ND	24	10	40
70N 46+50W	.3	4	ND	7	30	14	2.34	1	20	10	62
70N 46+75W	.7	3	ND	14	68	25	3.53	1	52	13	138
70N 47+00W	.3	7	ND	8	37	25	3.45	ND	25	14	74
70N 47+25W	.2	4	ND	12	36	35	3.07	1	27	13	51
70N 48+50W	.4	4	5	9	25	21	2.07	ND	17	9	50
70N 48+75W	.1	6	ND	8	25	26	2.44	ND	17	10	55
70N 49+00W	.1	3	ND	6	24	17	2.28	ND	17	12	76
70N 49+25W	.2	3	ND	9	32	28	3.04	ND	23	11	100
70N 49+50W	.3	8	5	8	25	30	2.20	ND	18	11	44
70N 49+75W	.3	4	ND	9	38	22	2.27	1	20	11	43
L76N 35+00W	.6	ND	ND	14	33	128	3.36	ND	30	12	120
L76N 35+25W	.7	ND	5	13	34	122	3.33	1	31	13	121
L76N 36+00W	.4	5	5	10	33	64	3.05	1	26	12	102
L76N 36+25W	.4	4	ND	9	33	75	3.03	1	23	12	62
L76N 36+50W	.6	8	5	30	38	599	4.90	2	49	19	92
L76N 36+75W	.4	6	ND	11	31	63	2.46	1	30	11	54
L76N 37+00W	.3	8	10	8	29	26	2.30	ND	15	11	40
L76N 37+25W	.4	4	10	6	24	15	2.15	1	13	8	53
L76N 37+50W	.4	4	ND	6	24	17	1.98	1	16	8	36
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU +PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PS PPM	ZN PPM
L76N 37+75W	.1	3	5	5	23	12	2.06	ND	12	8	44
L76N 38+00W	.1	6	ND	4	21	12	1.62	ND	9	10	36
L76N 38+25W	.1	7	ND	7	29	21	2.30	ND	17	9	51
L76N 38+50W	.1	5	ND	9	31	25	2.71	ND	24	14	73
L76N 38+75W	.1	ND	5	21	36	51	2.89	ND	26	18	101
L76N 39+00W	.1	ND	ND	11	29	36	2.40	ND	19	11	83
L76N 39+25W	.1	3	5	16	46	75	3.28	ND	35	16	104
L76N 41+00W	.9	ND	ND	24	45	168	4.14	2	35	22	106
L76N 41+25W	.2	6	5	13	35	63	2.99	ND	28	14	51
L76N 41+50W	.2	8	5	7	25	18	2.83	1	13	11	89
L76N 41+75W	.3	5	ND	4	18	8	1.82	1	6	12	37
L76N 42+00W	.2	5	ND	5	22	12	2.09	1	11	12	52
L76N 42+25W	.1	ND	5	10	37	44	3.25	1	31	16	93
L76N 42+50W	.1	ND	ND	10	37	29	3.77	1	23	17	89
L76N 42+75W	.1	ND	ND	8	34	33	3.27	1	23	13	96
L76N 43+00W	.2	4	ND	11	34	49	2.66	2	18	10	78
L76N 43+25W	.3	6	ND	10	41	49	3.33	2	30	16	50
L76N 43+50W	.2	3	ND	9	32	29	2.30	1	24	13	56
L76N 43+75W	.4	5	ND	5	25	11	2.08	1	11	13	49
L76N 44+00W	.2	5	ND	4	21	10	1.52	1	8	11	48
L76N 44+25W	.4	5	ND	8	30	22	1.92	1	25	12	47
L76N 44+50W	.4	4	ND	10	32	28	2.22	1	22	12	52
L76N 44+75W	.4	4	ND	8	32	29	2.35	1	22	12	51
L76N 45+00W	.4	3	ND	8	30	25	2.26	1	21	14	61
L76N 45+25W	.3	ND	25	8	39	21	2.17	1	18	12	59
L76N 45+50W	.3	3	5	10	34	26	2.98	1	22	12	67
L76N 45+75W	.4	4	5	10	37	28	2.69	ND	23	11	71
L76N 46+00W	.7	4	5	9	40	17	2.46	1	20	12	83
L76N 46+25W	.5	3	5	5	24	14	2.00	1	14	11	37
L76N 46+50W	.5	9	ND	6	25	15	2.00	1	17	12	43
L76N 46+75W	.3	7	ND	6	26	16	2.00	1	17	12	47
L76N 47+00W	.3	5	ND	8	28	17	1.91	ND	18	12	66
L76N 47+25W	.4	4	5	6	24	15	1.70	ND	15	11	43
L76N 48+00W	.4	4	5	9	32	21	2.58	1	21	13	77
L76N 48+25W	.4	3	10	8	31	21	2.67	1	20	14	82
L76N 48+50W	.4	7	5	8	31	35	2.60	1	21	15	68
L76N 48+75W	.6	7	10	8	36	24	2.89	1	16	16	81
L76N 49+00W	.6	5	5	11	37	20	2.70	1	21	14	131
L76N 49+25W	.6	8	10	14	24	90	3.31	1	13	14	64
DETECTION LIMIT	.1	3	45	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU +PPM	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L60N 40+75W	.1	ND	ND	2	12	4	.78	ND	3	9	15
L60N 41+00W	.1	ND	5	8	26	15	2.20	1	19	12	81
L60N 41+25W	.1	ND	10	7	19	17	2.04	1	15	12	54
L60N 41+50W	.1	ND	ND	5	18	9	1.47	1	9	11	48
L60N 41+75W	.1	3	20	6	19	14	1.66	1	15	13	58
L60N 42+00W	.1	ND	ND	3	13	6	1.22	ND	5	10	48
L60N 42+25W	.1	ND	ND	8	21	12	1.80	ND	12	12	72
L60N 42+75W	.1	ND	ND	9	31	17	2.24	ND	29	10	93
L60N 43+00W	.1	ND	ND	9	40	16	2.44	1	23	12	59
L60N 43+25W	.1	ND	5	7	27	14	2.02	1	16	11	93
L60N 43+50W	.1	ND	15	8	33	16	2.32	1	22	10	107
L60N 43+75W	.1	ND	ND	3	24	6	1.43	ND	7	9	29
L60N 44+00W	.1	ND	ND	6	28	15	2.53	ND	15	13	66
L60N 44+25W	.1	ND	ND	7	31	18	2.44	1	23	12	67
L60N 44+50W	.1	ND	ND	5	22	9	1.80	1	13	12	62
L60N 44+75W	.1	ND	ND	7	29	17	2.34	1	16	13	62
L60N 45+00W	.1	ND	ND	6	27	16	2.08	1	15	13	70
L60N 45+25W	.1	ND	ND	7	23	15	1.92	1	18	12	45
L60N 45+50W	.2	ND	ND	4	18	6	1.22	ND	8	11	34
L60N 45+75W	.2	ND	ND	7	23	13	1.80	1	16	12	36
L60N 46+00W	.3	ND	10	6	24	10	1.90	1	20	13	50
L60N 46+25W	.1	ND	10	7	26	10	2.07	1	18	15	123
L60N 46+50W	.1	ND	15	6	27	12	2.05	1	16	14	61
L60N 46+75W	.2	4	10	8	31	17	2.40	1	24	15	73
L60N 47+00W	.3	4	ND	6	24	12	1.90	1	9	17	80
L60N 47+25W	.4	ND	ND	7	31	10	1.98	1	14	14	48
L60N 47+50W	.2	3	40	9	34	13	2.19	1	15	13	94
L60N 47+75W	.3	ND	10	7	33	12	2.15	1	19	14	62
L60N 48+00W	.3	4	ND	9	29	19	2.46	1	25	16	49
L60N 48+25W	.1	3	ND	8	28	15	2.71	1	19	16	85
L60N 48+50W	.3	4	ND	4	18	7	1.50	1	8	16	46
L60N 48+75W	.4	4	ND	9	30	15	2.30	1	19	18	79
L60N 49+00W	.4	7	ND	8	25	18	1.91	1	14	25	43
L60N 49+50W	.4	7	15	11	39	31	2.62	1	31	17	45
L60N 49+50W	.2	ND	ND	16	17	114	3.61	1	20	23	139
L60N 49+75W	.1	4	10	13	25	65	3.24	1	24	20	81
L60N 50+00W	.1	ND	5	16	28	91	3.78	1	34	23	106
L62N 30+00W	.6	8	5	7	24	14	1.85	1	18	15	49
L62N 30+25W	.4	9	ND	8	25	17	2.02	1	21	16	53
DETECTION LIMIT	.1	3	45	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPE	CD PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L62N 30+50W	.3	ND	10	7	23	14	1.81	1	18	8	46
L62N 30+75W	.3	ND	10	11	34	22	2.46	ND	27	7	56
L62N 31+00W	.3	ND	10	10	31	21	2.37	ND	24	20	55
L62N 31+25W	.3	ND	10	10	32	22	2.41	1	24	8	54
L62N 31+50W	.1	ND	5	10	38	36	2.87	ND	32	13	61
L62N 31+75W	.3	ND	ND	8	31	32	2.33	ND	27	15	47
L62N 32+00W	.3	ND	ND	7	26	14	2.00	ND	19	9	54
L62N 32+25W	.2	ND	ND	11	42	16	2.57	1	26	17	72
L62N 32+50W	.4	ND	ND	7	24	13	1.85	ND	15	8	46
L62N 32+75W	.3	ND	ND	6	25	14	1.89	1	17	8	46
L62N 33+00W	.3	ND	ND	9	28	16	1.94	1	17	10	51
L62N 33+25W	.3	ND	10	8	30	22	2.15	ND	19	11	64
L62N 33+50W	.1	3	5	7	17	112	2.59	1	18	14	51
L62N 33+75W	.4	ND	ND	14	36	49	3.15	1	39	11	66
L62N 34+00W	.4	ND	ND	14	34	47	3.14	ND	36	12	65
L62N 34+25W	.3	ND	ND	18	31	79	3.71	1	29	11	65
L62N 34+50W	.3	ND	ND	19	31	84	3.88	ND	28	12	66
L62N 34+75W	.3	ND	15	20	35	89	4.10	1	32	13	69
L62N 35+75W	.3	ND	15	7	27	14	2.10	1	20	12	51
L62N 36+75W	.4	ND	ND	8	30	24	2.13	1	25	11	43
L62N 37+00W	.3	ND	10	7	31	21	2.10	1	20	9	41
L62N 37+25W	.4	ND	15	6	23	20	1.87	1	11	17	41
L62N 37+75W	.3	ND	10	7	30	17	2.27	1	20	9	39
L62N 38+00W	.2	ND	15	17	32	44	2.51	ND	24	13	47
L62N 38+25W	.4	ND	5	6	22	14	1.54	1	12	11	36
L62N 38+50W	.3	ND	5	6	29	18	2.21	1	16	13	44
L62N 38+75W	.4	ND	5	4	22	13	1.65	ND	11	10	33
L62N 39+00W	.1	ND	5	6	34	27	2.56	1	20	12	53
L62N 39+25W	.3	ND	ND	7	28	12	2.20	1	18	10	81
L62N 39+50W	.6	ND	ND	4	17	11	1.19	1	9	12	40
L62N 39+75W	.4	ND	ND	3	15	7	1.19	ND	6	13	23
L62N 40+00W	.3	ND	ND	5	21	27	1.47	1	17	11	36
L62N 40+25W	.4	ND	ND	5	26	13	2.38	1	13	12	99
L62N 40+50W	.3	ND	ND	7	35	14	2.43	1	18	11	124
L62N 40+75W	.3	ND	ND	9	31	24	2.40	1	23	9	64
L62N 41+00W	.3	5	ND	9	29	44	2.45	1	20	12	49
L62N 41+25W	.3	ND	ND	10	27	46	2.50	1	20	17	52
L62N 41+50W	.5	ND	ND	9	31	26	2.57	1	23	11	53
L62N 41+75W	.5	ND	ND	8	29	25	2.44	1	21	13	63
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE 1	MG PPM	NI PPM	PR PPM	ZN PPM
L62N 42+00W	.3	ND	ND	6	23	15	2.26	ND	16	9	60
L62N 42+25W	.2	5	ND	6	25	17	2.25	ND	17	13	49
L62N 42+50W	.2	3	ND	9	31	25	2.72	ND	20	12	64
L62N 42+75W	.1	ND	ND	11	30	34	2.49	ND	24	10	49
L62N 43+00W	.3	ND	ND	8	31	21	2.56	ND	20	17	53
L62N 43+25W	.2	3	ND	9	29	20	2.54	1	20	8	57
L62N 44+25W	.1	3	ND	4	6	32	.97	1	5	22	75
L62N 44+50W	.3	ND	ND	11	46	20	3.00	2	31	12	93
L62N 44+75W	.2	3	ND	9	31	19	2.38	1	23	11	74
L62N 45+00W	.2	ND	ND	10	32	22	2.46	ND	22	11	76
L62N 45+25W	.2	ND	ND	44	16	133	6.49	1	24	10	169
L62N 45+50W	.2	ND	ND	42	15	119	6.42	1	23	10	156
L62N 45+75W	.4	3	ND	8	35	15	2.27	ND	21	10	69
L62N 46+00W	.3	ND	ND	9	35	17	2.38	1	24	15	79
L62N 46+75W	.3	ND	ND	14	41	30	3.39	ND	34	13	116
L62N 47+00W	.3	3	ND	8	27	11	2.14	1	16	13	76
L62N 47+25W	.5	ND	ND	6	25	12	1.94	1	12	11	46
L62N 47+50W	.4	5	ND	9	28	17	2.41	1	17	12	86
L62N 47+75W	.1	ND	5	8	19	18	2.01	1	19	26	126
L62N 48+00W	.5	ND	ND	6	23	15	1.73	1	18	10	44
L62N 48+25W	.3	4	ND	4	19	12	1.81	1	9	12	40
L62N 48+50W	.3	ND	ND	6	23	14	2.08	2	10	9	46
L62N 48+75W	.3	5	ND	10	31	31	2.64	ND	24	18	75
L62N 49+00W	.3	5	ND	11	34	31	2.94	1	25	14	100
L62N 49+25W	.5	4	ND	6	29	12	2.23	1	12	10	52
L62N 49+50W	.5	3	ND	10	40	22	2.96	2	24	14	76
L62N 49+75W	.6	3	ND	6	29	12	2.11	4	10	11	39
L62N 50+00W	.5	ND	ND	9	39	21	2.82	2	23	11	82
L64N 30+00W	.3	ND	ND	10	30	20	2.47	1	23	9	47
L64N 30+25W	.2	ND	ND	8	35	27	2.71	2	27	13	63
L64N 30+50W	.4	4	ND	8	27	16	2.00	2	18	16	39
L64N 30+75W	.4	6	ND	6	27	13	2.11	1	15	13	41
L64N 31+00W	.5	5	ND	7	27	16	2.16	ND	17	14	41
L64N 31+25W	.4	6	ND	9	34	28	2.49	1	26	12	46
L64N 31+50W	.4	4	ND	9	37	31	2.73	ND	27	12	50
L64N 31+75W	.5	ND	ND	9	31	24	2.34	1	22	12	61
L64N 32+00W	.5	5	ND	11	34	28	2.68	1	27	13	60
L64N 32+25W	.5	5	ND	12	35	28	2.82	1	28	15	58
L64N 32+75W	.3	3	ND	10	27	15	2.12	1	20	10	61
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CD PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L64N 33+00W	.3	4	ND	5	28	11	2.43	ND	18	20	53
L64N 33+25W	.2	6	ND	6	30	12	2.51	ND	20	16	73
L64N 33+50W	.4	7	ND	7	30	27	2.20	ND	25	15	47
L64N 33+75W	.3	7	ND	9	36	39	2.71	ND	32	15	55
L64N 34+00W	.2	3	ND	6	25	15	1.75	ND	21	13	46
L64N 34+75W	.2	3	5	23	44	33	3.14	ND	34	19	102
L64N 35+00W	.2	5	ND	7	31	16	2.01	1	19	12	46
L64N 35+25W	.2	6	ND	5	24	12	2.12	1	17	6	40
L64N 35+50W	.3	9	ND	6	24	10	1.96	ND	14	17	49
L64N 36+00W	.3	8	ND	9	29	31	2.42	ND	23	16	48
L64N 36+25W	.4	7	ND	11	38	45	3.09	1	34	37	58
L64N 36+50W	.3	ND	ND	7	30	19	2.00	ND	19	11	50
L64N 36+75W	.3	4	ND	7	28	19	1.97	ND	19	9	46
L64N 37+00W	.2	6	ND	8	33	22	2.69	ND	23	17	55
L64N 37+25W	.3	5	ND	6	27	14	2.07	ND	17	18	56
L64N 37+50W	.4	3	ND	7	35	20	2.67	ND	24	14	69
L64N 37+75W	.3	6	ND	8	30	17	2.48	ND	26	11	72
L64N 38+00W	.3	9	ND	4	20	21	1.50	ND	12	14	42
L64N 38+25W	.3	8	ND	4	18	11	1.59	ND	11	10	30
L64N 38+50W	.3	5	ND	6	25	24	2.16	ND	18	12	75
L64N 38+75W	.4	8	ND	7	28	30	2.31	ND	24	14	78
L64N 39+00W	.3	ND	ND	6	29	17	2.36	ND	17	14	62
L64N 39+25W	.3	5	ND	5	20	18	1.96	ND	15	11	52
L64N 39+50W	.4	6	ND	4	18	11	1.79	1	10	19	52
L64N 39+75W	.5	7	ND	9	31	36	2.66	ND	27	11	56
L64N 40+00W	.3	5	ND	5	26	17	1.93	ND	14	12	46
L64N 40+25W	.3	5	ND	8	24	19	2.06	1	19	11	62
L64N 40+50W	.3	ND	ND	9	32	27	2.81	1	33	9	117
L64N 40+75W	.3	5	ND	7	25	27	2.15	ND	19	9	61
L64N 41+00W	.3	10	ND	11	28	41	2.70	1	25	17	59
L64N 41+25W	.3	6	ND	6	23	24	2.16	1	20	11	64
L64N 41+50W	.3	5	ND	5	21	17	2.04	1	12	14	46
L64N 41+75W	.4	10	ND	4	21	16	1.52	ND	14	11	35
L64N 42+00W	.4	4	ND	5	24	22	1.65	ND	17	13	43
L64N 42+25W	.3	3	ND	8	32	36	2.35	ND	25	17	70
L64N 42+50W	.3	7	ND	7	25	19	2.02	ND	16	12	47
L64N 42+75W	.3	ND	ND	14	43	60	3.24	ND	39	14	97
L64N 43+00W	.8	8	15	19	61	131	4.62	ND	63	20	119
L64N 43+25W	.4	7	5	9	27	24	2.40	ND	19	14	47
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE 1	MG PPM	NI PPM	FE PPM	ZN PPM
L64N 43+50W	.1	6	ND	4	21	10	1.28	1	10	12	36
L64N 43+75W	.1	ND	ND	7	26	13	2.37	1	15	13	86
L64N 44+00W	.1	6	ND	6	35	12	2.42	1	14	13	66
L64N 44+25W	.1	6	ND	9	24	19	2.42	1	16	13	134
L64N 44+50W	.1	4	ND	8	24	20	2.60	2	13	13	124
L64N 45+00W	.1	10	10	9	28	23	2.63	1	22	17	68
L64N 45+25W	.2	4	ND	21	32	106	4.09	1	28	18	133
L64N 45+50W	.1	ND	ND	8	33	26	2.96	ND	24	14	89
L64N 45+75W	.1	5	ND	7	33	15	2.27	1	14	12	47
L64N 46+00W	.1	4	10	9	44	99	2.00	2	38	19	57
L64N 46+25W	.1	6	ND	9	33	26	2.79	ND	25	22	55
L64N 46+50W	.1	8	ND	5	9	37	1.33	1	9	48	140
L64N 47+25W	.1	7	ND	11	26	19	2.55	1	17	17	183
L64N 47+50W	.1	3	ND	6	23	15	2.20	ND	16	14	74
L64N 48+00W	.1	7	ND	9	28	21	2.40	2	19	15	68
L64N 48+25W	.1	ND	ND	8	24	18	2.12	2	16	12	55
L64N 48+50W	.1	4	ND	7	24	17	2.47	1	12	12	71
L64N 48+75W	.1	7	ND	7	26	22	2.36	1	17	13	51
L64N 49+00W	.1	4	ND	6	23	19	2.11	1	15	13	54
L64N 49+25W	.1	9	ND	7	26	13	2.03	ND	10	11	45
L64N 49+50W	.2	6	ND	7	24	21	2.09	ND	23	12	53
L64N 49+75W	.1	3	ND	6	23	11	1.93	ND	14	11	36
L68N 47+00W	.1	3	ND	7	24	21	2.15	ND	16	17	47
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

VANGEOCHEM LAB LIMITED

MAIN OFFICE: 1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604)986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -= NOT ANALYZED, +AU= GEOCHEM

COMPANY: E&B EXPLORATIONS REPORT#: 860363PA DATE RECEIVED: 86/08/11
 ATTENTION: L.SALEKEN & M.TINDALL JOB#: 860363 DATE COMPLETED: 86/08/20
 PROJECT: 5061-CB PO#5538 INVOICE#: 860363NA COPY SENT TO: VANC.OFFICE

ANALYST W. Adams

PAGE 1 OF 6

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CD PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L60N 30+00W	.2	5	5	8	27	19	2.34	1	25	11	51
L60N 30+75W	.3	4	ND	12	44	52	3.21	1	41	16	50
L60N 31+00W	.2	3	ND	14	37	50	3.19	ND	38	13	66
L60N 31+25W	.3	3	ND	12	38	47	3.12	ND	36	15	62
L60N 31+50W	.4	3	ND	13	47	62	3.65	ND	45	16	68
L60N 31+75W	.3	ND	ND	10	41	18	2.75	1	23	12	84
L60N 32+00W	.3	4	ND	10	37	18	2.52	1	19	14	82
L60N 32+25W	.2	5	ND	11	39	19	2.53	1	20	12	79
L60N 32+50W	.3	3	ND	9	31	16	2.63	1	23	12	85
L60N 32+75W	.2	3	ND	9	29	31	2.12	ND	23	13	55
L60N 33+00W	.3	4	ND	8	27	20	1.98	ND	20	13	49
L60N 33+25W	.3	5	ND	12	30	45	2.61	ND	29	13	54
L60N 33+50W	.5	ND	ND	8	26	15	2.07	ND	20	14	55
L60N 33+75W	.2	5	ND	7	23	11	1.83	ND	15	11	43
L60N 34+00W	.3	ND	ND	4	21	8	1.67	1	10	12	37
L60N 34+25W	.4	3	ND	5	24	10	1.82	ND	14	13	38
L60N 34+50W	.4	7	ND	7	26	12	1.87	ND	16	13	45
L60N 34+75W	.2	3	ND	7	24	11	2.14	ND	17	13	60
L60N 35+00W	.2	3	ND	5	20	8	1.69	ND	11	10	43
L60N 35+25W	.4	ND	ND	11	36	30	2.64	ND	32	14	70
L60N 35+50W	.4	ND	10	5	21	8	1.60	1	20	13	39
L60N 35+75W	.4	5	ND	2	13	7	.94	1	3	13	32
L60N 36+00W	.3	3	ND	6	27	14	2.47	ND	19	14	67
L60N 36+25W	.3	5	ND	4	19	10	1.78	1	11	15	40
L60N 36+50W	.3	4	ND	5	23	11	1.95	ND	17	13	46
L60N 36+75W	.3	7	ND	6	25	7	1.57	ND	12	10	44
L60N 37+00W	.3	4	ND	4	23	8	1.71	ND	9	12	47
L60N 37+25W	.4	ND	5	10	35	31	2.59	ND	26	14	67
L60N 38+00W	.4	3	5	8	28	14	2.03	ND	15	11	33
L60N 38+25W	.3	3	5	7	27	16	2.13	ND	18	13	58
L60N 38+50W	.2	ND	10	9	31	24	2.64	ND	22	14	63
L60N 38+75W	.3	3	ND	4	22	10	1.50	ND	10	12	39
L60N 39+00W	.4	4	ND	5	21	15	1.95	ND	10	11	74
L60N 39+25W	.1	ND	ND	21	47	87	4.25	1	44	24	100
L60N 39+50W	.2	ND	ND	13	23	32	2.11	ND	17	15	61
L60N 39+75W	.5	5	ND	5	17	9	1.65	ND	6	14	26
L60N 40+00W	.5	ND	ND	8	30	25	2.90	ND	23	15	32
L60N 40+25W	.3	3	ND	9	30	20	2.79	ND	25	15	151
L60N 40+50W	.4	ND	ND	5	15	14	1.65	ND	10	10	50
DETECTION LIMIT	.3	3	45	1	1	1	.01	1	1	1	3

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CD PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L70N 56+50W	.1	8	ND	6	27	17	2.13	2	17	11	41
L70N 56+75W	.1	7	ND	6	28	16	2.16	2	16	11	38
L70N 57+00W	.2	9	ND	7	31	25	2.55	2	18	14	54
L70N 57+25W	.1	8	ND	8	33	26	2.80	2	20	13	59
L70N 57+50W	.2	9	5	14	42	55	3.38	2	38	21	70
L70N 57+75W	.1	10	ND	9	29	41	2.53	3	22	15	61
L70N 58+00W	.1	3	5	10	37	37	3.23	2	26	19	176
L70N 58+25W	.1	ND	ND	4	16	15	1.75	1	9	10	225
L70N 58+50W	.1	6	ND	5	18	17	2.06	ND	11	12	71
L70N 58+75W	.3	8	ND	8	28	25	2.38	ND	18	15	95
L70N 59+00W	.1	5	5	6	24	19	1.98	1	11	14	72
L70N 59+25W	.4	8	10	8	25	29	2.28	1	14	18	65
L70N 59+50W	.1	4	10	10	31	41	2.44	1	18	14	72
L70N 59+75W	.3	7	10	8	34	26	2.20	2	22	13	55
L70N 60+00W	.1	4	ND	8	33	24	2.16	3	19	12	54
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

VANGEOCHEM LAB LIMITED

Paul Stealy

MAIN OFFICE: 1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604)986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -- NOT ANALYZED. *AU= GEOCHEM

COMPANY: E&B EXPLORATIONS REPORT#: 860374PA DATE RECEIVED: 86/08/18
 ATTENTION: L.SALEKEN & M.TINDALL JOB#: 860374 DATE COMPLETED: 86/08/22
 PROJECT: 5061-CB P0# 5545 INVOICE#: 860374NA COPY SENT TO: VANC.OFFICE

ANALYST W. Reeves

PAGE 1 OF 12

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L50N 34+00W	.1	4	ND	4	19	5	1.58	1	11	11	45
L50N 34+25W	.1	3	ND	5	23	10	1.98	1	14	10	44
L50N 34+50W	.2	5	ND	6	24	14	2.08	ND	15	10	37
L50N 34+75W	.2	7	ND	6	23	11	2.09	1	13	12	45
L50N 35+00W	.2	7	ND	7	26	10	2.30	ND	16	12	54
L50N 35+25W	.2	6	ND	7	26	15	2.05	ND	17	12	39
L50N 35+50W	ND	ND	ND	8	21	21	2.58	ND	16	15	84
L50N 35+75W	ND	ND	ND	14	20	50	2.80	ND	11	16	177
L50N 36+00W	.3	8	ND	6	23	15	1.96	ND	15	13	55
L50N 36+25W	.5	3	ND	8	29	17	2.47	1	21	16	54
L50N 36+50W	.6	5	ND	6	22	11	1.81	2	13	13	44
L50N 36+75W	.6	4	ND	6	22	12	1.89	1	14	14	44
L50N 37+00W	.5	8	ND	8	25	17	2.14	1	18	14	43
L50N 37+25W	.4	6	ND	8	25	17	2.25	1	18	14	54
L50N 37+50W	.3	ND	ND	9	25	17	2.38	1	20	14	73
L50N 37+75W	.4	3	ND	6	23	12	1.91	2	14	12	45
L50N 38+00W	.3	3	ND	10	26	24	2.38	2	24	13	53
L50N 38+25W	.4	7	5	6	22	16	1.93	2	17	13	42
L50N 38+50W	.4	4	ND	8	25	20	2.22	1	20	17	46
L50N 38+75W	.4	4	ND	9	25	21	2.10	2	19	14	54
L50N 39+00W	.3	6	ND	8	26	17	2.40	1	27	14	56
L50N 39+25W	.3	4	ND	10	28	23	2.44	ND	20	14	53
L50N 39+50W	.4	6	ND	6	24	15	2.42	ND	14	15	44
L50N 39+75W	.4	6	ND	8	24	17	2.37	ND	18	15	42
L50N 40+00W	.3	5	ND	8	26	17	2.50	1	18	14	46
L50N 40+25W	.2	ND	ND	9	43	20	2.35	ND	24	13	57
L50N 40+50W	.1	5	ND	8	27	17	2.47	1	16	13	54
L50N 40+75W	.1	ND	ND	7	24	13	2.42	1	14	13	49
L50N 41+00W	.2	6	ND	9	25	23	2.42	ND	20	16	48
L50N 41+25W	.2	5	ND	10	30	21	2.91	1	21	14	48
L50N 41+50W	.1	5	ND	10	30	25	2.93	1	24	15	48
L50N 41+75W	.2	4	ND	11	29	21	2.68	1	19	14	50
L50N 42+00W	.2	6	ND	10	29	23	2.56	1	19	16	46
L50N 42+25W	.2	ND	ND	8	23	19	2.43	1	16	12	47
L50N 42+50W	.1	5	10	8	25	20	2.40	1	18	13	45
L50N 42+75W	.3	8	ND	8	27	21	2.48	1	20	15	54
L50N 43+00W	.2	ND	ND	9	30	26	2.59	2	22	14	54
L50N 43+25W	.2	6	ND	9	29	24	2.44	1	22	14	51
L50N 43+50W	ND	ND	ND	9	32	17	2.59	2	20	13	51
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

RECEIVED
AUG 25 1986
TESTS

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L50N 43+75W	.1	6	10	7	26	17	2.23	2	17	8	49
L50N 44+00W	.2	8	ND	5	20	12	1.88	1	13	9	44
L50N 44+25W	.1	12	ND	11	32	28	2.74	2	26	11	52
L50N 45+00W	.2	7	ND	8	37	19	2.57	1	20	11	81
L50N 45+25W	.1	8	ND	8	31	22	2.55	1	20	10	54
L50N 45+50W	.1	5	ND	6	28	15	2.61	1	18	8	48
L50N 45+75W	.1	5	ND	7	31	20	2.63	2	23	10	52
L50N 46+00W	.1	7	ND	9	33	19	2.77	2	22	10	53
L50N 46+25W	.1	7	ND	9	29	25	2.42	1	20	11	57
L50N 46+50W	.3	9	ND	11	34	45	2.66	1	28	11	69
L50N 46+75W	.1	8	ND	8	28	21	2.59	1	19	10	64
L50N 47+25W	.1	9	ND	8	33	24	2.60	1	25	9	60
L50N 47+50W	.3	ND	ND	5	20	15	1.84	ND	13	10	58
L50N 47+75W	.1	6	ND	5	20	10	1.90	2	11	8	54
L50N 48+00W	.2	5	ND	8	23	11	2.21	1	11	12	74
L50N 48+25W	.1	ND	ND	6	29	15	2.37	1	13	11	121
L50N 48+50W	.3	5	ND	7	30	22	2.37	2	20	11	61
L50N 48+75W	.1	4	ND	8	27	24	2.67	1	19	11	67
L50N 49+25W	.1	4	ND	9	27	14	2.71	1	19	14	66
L50N 49+75W	.3	3	ND	15	26	21	2.20	2	16	14	64
L50N 50+25W	.3	ND	ND	8	41	12	2.31	2	30	12	86
L50N 50+50W	.2	4	ND	8	30	14	2.34	1	22	10	89
L50N 50+75W	.1	ND	5	8	30	20	2.75	1	20	9	59
L50N 51+00W	.3	6	ND	7	30	13	2.50	3	18	10	82
L50N 51+25W	.4	6	ND	7	28	17	2.34	2	17	12	52
L50N 51+50W	.1	7	ND	11	36	31	2.94	1	26	13	47
L50N 51+75W	.4	6	5	6	32	14	2.70	2	16	13	62
L50N 52+00W	.3	3	ND	6	29	11	2.19	1	13	12	42
L52N 45+00W	.2	10	ND	10	35	20	2.61	ND	23	13	64
L52N 45+50W	.4	7	ND	9	31	14	2.48	2	15	11	59
L52N 45+75W	.2	4	ND	5	26	16	1.78	1	13	9	49
L52N 46+00W	.1	7	ND	8	34	27	3.11	2	22	12	58
L52N 46+25W	.1	ND	ND	7	22	12	1.84	1	12	10	75
L52N 46+50W	.1	8	ND	8	32	18	2.62	3	23	11	63
L52N 46+75W	.2	5	ND	8	30	17	2.56	2	19	10	74
L52N 47+00W	.2	8	ND	9	30	16	2.33	2	19	10	57
L52N 47+25W	.3	8	ND	8	30	13	2.42	3	23	10	75
L52N 47+50W	.1	4	ND	7	28	11	2.16	2	16	13	64
L52N 47+75W	.1	8	ND	7	29	21	2.69	2	19	11	55
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L54N 42+00W	.1	ND	5	7	28	17	2.14	1	23	10	46
L54N 42+25W	.1	3	25	7	27	16	2.11	1	24	10	49
L54N 42+50W	.1	3	5	7	20	9	1.71	1	14	11	55
L54N 42+75W	.3	5	5	8	25	15	2.12	3	18	11	49
L54N 43+00W	.3	5	15	8	27	15	2.21	2	21	12	50
L54N 43+25W	.4	4	ND	7	26	18	2.26	2	18	14	47
L54N 43+50W	.2	3	ND	6	23	14	1.92	2	15	10	47
L54N 43+75W	.3	ND	ND	12	34	33	2.68	1	29	15	77
L54N 44+00W	.3	ND	ND	9	30	29	2.33	1	24	12	61
L54N 44+25W	.1	ND	ND	14	41	54	3.32	1	38	16	79
L54N 44+50W	.2	5	ND	8	30	18	2.34	1	19	11	73
L54N 44+75W	.4	4	5	11	36	45	3.12	1	34	15	63
L54N 45+00W	.3	5	10	13	39	51	3.42	ND	36	15	69
L54N 45+25W	.1	4	ND	9	35	19	2.42	1	22	13	46
L54N 45+50W	.3	ND	ND	10	48	26	2.65	2	26	13	54
L54N 45+75W	.2	ND	5	10	41	27	2.51	1	27	13	56
L54N 46+00W	.2	5	ND	8	35	17	2.66	2	20	13	48
L54N 46+25W	.2	5	ND	9	30	23	2.85	1	22	13	40
L54N 46+50W	.1	5	ND	9	27	18	2.43	2	16	11	49
L54N 46+75W	.3	7	ND	11	30	23	2.78	1	19	13	45
L54N 47+00W	.3	6	5	10	31	25	2.75	2	28	14	45
L54N 47+25W	.2	ND	5	10	28	23	2.58	2	21	13	82
L54N 47+50W	.2	8	5	11	30	23	2.67	2	21	15	150
L54N 47+75W	.1	6	ND	15	40	42	2.71	3	34	15	72
L54N 48+00W	.3	8	20	10	41	28	3.16	2	26	15	57
L54N 48+25W	.2	8	5	9	39	25	2.95	2	25	16	55
L54N 48+50W	.5	9	ND	5	18	9	1.63	3	10	12	51
L54N 48+75W	.5	9	ND	6	24	12	2.07	1	15	13	50
L54N 49+00W	.3	3	ND	10	42	20	2.60	2	29	14	55
L54N 49+25W	.4	4	10	7	33	12	2.16	1	18	13	79
L54N 49+50W	.4	9	5	9	27	17	2.20	2	21	14	64
L54N 49+75W	.5	8	5	7	27	14	2.30	2	20	14	52
L54N 50+00W	.4	8	ND	9	30	16	2.36	1	27	14	58
L54N 50+25W	.4	ND	5	11	26	16	2.25	2	38	21	105
L54N 50+50W	.1	8	ND	11	25	35	2.69	1	26	37	115
L54N 50+75W	.2	5	ND	8	26	20	2.21	1	27	19	97
L54N 51+00W	.4	7	5	9	28	20	2.20	1	19	16	65
L54N 51+25W	.4	7	10	6	27	15	1.88	1	19	13	45
L54N 51+50W	.5	8	5	9	25	19	2.24	2	17	14	45
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CD PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L58N 53+50W	.1	8	ND	10	35	23	2.91	ND	25	11	55
L58N 53+75W	.1	8	ND	9	33	21	2.81	2	25	7	62
L58N 54+00W	.1	ND	ND	8	21	33	2.30	2	19	10	61
L58N 54+25W	.1	ND	ND	10	30	16	2.53	ND	18	9	74
L58N 54+50W	.1	4	ND	11	35	18	2.76	1	25	11	106
L58N 54+75W	.1	ND	ND	11	36	17	2.76	ND	25	10	110
L58N 55+25W	.1	5	ND	9	39	23	3.03	ND	27	11	96
L58N 55+50W	.1	ND	ND	11	51	23	3.29	ND	29	11	131
L58N 55+75W	.1	5	ND	8	43	19	2.89	ND	27	11	87
L58N 56+00W	.2	5	ND	8	38	18	2.34	ND	28	10	76
L58N 56+25W	.2	7	ND	9	34	21	2.55	2	24	11	67
L58N 56+50W	.2	4	5	10	34	26	2.39	1	24	10	51
L58N 56+75W	.1	8	10	11	42	31	2.69	ND	27	10	55
L58N 57+00W	.1	ND	10	10	35	24	2.45	ND	23	8	69
L58N 58+00W	.1	ND	10	10	34	29	2.79	ND	26	12	113
L58N 58+25W	.1	3	15	12	39	43	3.34	ND	32	16	87
L58N 58+50W	.1	4	5	9	28	17	2.37	ND	19	9	83
L58N 58+75W	.1	4	5	8	27	23	2.48	1	21	10	65
L58N 59+00W	.1	4	ND	8	34	15	2.33	1	17	11	61
L58N 59+25W	.1	3	5	12	39	25	3.20	ND	26	14	112
L58N 59+50W	.2	5	5	9	34	16	2.66	ND	28	11	82
L58N 59+75W	.2	6	ND	10	42	20	2.59	ND	26	9	65
L58N 60+00W	.2	ND	5	13	47	34	2.80	2	35	10	70
L60N 50+25W	.2	ND	15	14	15	76	2.86	ND	37	22	106
L60N 50+50W	.1	ND	ND	10	21	49	2.46	ND	24	14	66
L60N 50+75W	.1	6	10	10	33	43	2.87	ND	25	14	53
L60N 51+00W	.1	4	5	10	30	38	2.68	ND	24	12	51
L60N 51+25W	.3	6	5	10	29	33	2.52	ND	22	13	74
L60N 51+50W	.2	ND	10	8	25	17	2.24	ND	20	10	47
L60N 51+75W	.1	4	ND	8	24	16	2.28	ND	15	10	69
L60N 52+00W	.1	3	5	7	22	13	2.13	ND	15	9	64
L60N 52+25W	.4	5	ND	8	33	23	2.50	ND	19	10	51
L60N 52+50W	.5	6	ND	10	45	54	2.64	ND	29	13	46
L60N 53+00W	.4	6	5	10	44	55	2.67	ND	29	13	47
L60N 53+25W	.2	5	ND	9	29	39	2.84	ND	20	11	36
L60N 53+50W	.1	4	ND	7	19	23	2.09	ND	17	11	74
L60N 53+75W	.1	9	ND	13	45	48	3.16	ND	30	14	60
L60N 54+25W	.1	5	ND	10	32	26	2.46	ND	22	9	51
L60N 54+50W	.2	5	5	7	24	17	2.23	ND	15	11	53
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L60N 54+75W	.1	14	10	11	32	62	3.01	ND	32	14	52
L60N 55+00W	.1	8	5	9	30	33	2.26	2	22	11	60
L60N 55+25W	.1	12	5	8	30	20	2.65	2	24	8	67
L60N 55+50W	.1	10	ND	8	27	24	2.22	2	23	10	56
L60N 55+75W	.1	9	5	7	25	14	2.16	1	17	11	76
L60N 56+00W	.2	26	10	8	30	25	2.84	ND	21	14	85
L60N 56+25W	.2	8	5	11	38	28	2.86	1	32	12	50
L60N 56+50W	.5	8	5	7	32	15	2.14	ND	20	10	54
L60N 56+75W	.3	10	15	10	32	40	2.60	2	27	14	51
L60N 57+00W	.4	8	5	11	38	25	2.46	1	33	12	81
L60N 57+25W	.3	10	10	9	28	35	2.27	ND	23	17	51
L60N 57+50W	.4	11	15	10	29	35	2.48	2	27	16	52
L60N 57+75W	.5	7	5	10	47	24	2.48	ND	30	12	53
L60N 58+00W	.4	11	10	10	37	35	2.43	ND	26	14	54
L60N 58+50W	.4	7	10	10	31	30	2.41	ND	24	13	48
L60N 58+75W	.4	5	ND	10	43	20	2.61	ND	25	12	104
L60N 59+00W	.3	7	ND	10	30	27	2.32	ND	23	13	54
L60N 59+25W	.4	9	ND	9	29	24	2.13	1	22	12	50
L60N 59+50W	.4	11	10	12	32	42	2.77	1	29	16	52
L60N 59+75W	.5	10	5	13	36	56	3.15	ND	36	19	56
L60N 60+00W	.3	5	ND	9	24	19	2.11	ND	22	11	52
L62N 50+25W	.4	7	ND	7	24	11	1.82	ND	13	11	43
L62N 50+50W	.3	4	ND	10	32	29	2.41	ND	25	13	56
L62N 50+75W	.4	6	ND	6	25	12	2.02	ND	12	11	48
L62N 51+00W	.5	6	ND	6	22	15	1.89	ND	13	13	49
L62N 51+25W	.5	8	ND	6	25	14	2.01	1	15	12	44
L62N 51+50W	.3	7	ND	4	16	16	1.44	1	6	8	25
L62N 51+75W	.3	9	10	7	24	17	2.04	ND	18	10	35
L62N 52+00W	.3	7	ND	7	23	15	1.98	ND	17	11	35
L62N 52+25W	.3	4	ND	7	23	13	2.03	ND	14	12	84
L62N 52+50W	.6	8	10	13	36	31	3.11	2	35	17	73
L62N 52+75W	.1	16	5	2	4	29	.73	3	3	38	42
L62N 53+00W	.4	4	5	7	25	17	2.14	1	14	14	43
L62N 53+25W	.3	6	5	6	19	16	1.91	ND	14	11	85
L62N 53+50W	.2	3	10	7	39	10	1.80	2	15	12	81
L62N 53+75W	.1	4	10	9	25	40	2.35	2	21	22	63
L62N 54+00W	.3	3	5	8	27	19	2.47	1	17	12	46
L62N 54+25W	.5	8	5	8	25	40	2.47	ND	25	14	55
L62N 54+50W	.4	7	5	6	28	12	2.21	1	13	14	66
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE Z	MO PPM	NI PPM	PB PPM	ZN PPM
L62N 54+75W	.4	5	ND	7	28	17	2.24	1	13	12	33
L62N 55+25W	.1	8	10	13	25	104	3.20	1	26	26	100
L62N 55+50W	.3	5	20	8	25	17	2.47	1	13	12	51
L62N 55+75W	.4	4	ND	12	45	24	2.82	1	26	18	90
L62N 56+00W	.2	9	5	10	42	33	3.23	1	26	13	58
L62N 56+25W	.1	4	10	6	28	20	2.38	1	22	14	73
L62N 56+50W	.2	5	10	6	25	18	2.46	1	14	10	90
L62N 56+75W	.1	6	10	10	34	24	2.61	1	19	12	66
L62N 57+00W	.3	6	ND	5	32	11	1.72	1	7	10	44
L62N 57+25W	.5	6	ND	6	26	16	2.26	1	14	13	74
L62N 57+50W	.2	8	10	10	27	46	2.79	1	19	15	45
L62N 57+75W	.2	7	ND	6	34	13	2.01	ND	14	11	48
L62N 5+00W	.1	4	ND	6	37	11	1.96	1	12	10	60
L62N 58+25W	.2	ND	ND	7	40	14	2.05	1	14	9	66
L62N 58+50W	.1	ND	ND	8	40	16	2.31	1	20	9	63
L62N 58+75W	.1	ND	ND	12	34	24	2.98	ND	28	14	105
L62N 59+00W	.1	5	ND	7	22	21	2.34	1	15	14	83
L62N 59+25W	.3	5	5	8	30	12	2.20	1	13	12	67
L62N 59+50W	.3	5	ND	7	29	13	2.06	1	12	9	64
L62N 59+75W	.1	5	ND	8	27	44	2.46	ND	18	12	53
L62N 60+00W	.1	3	ND	5	27	13	1.96	1	18	10	52
L64N 50+25W	.2	4	ND	6	22	9	2.03	1	13	11	42
L64N 50+50W	.3	ND	ND	8	29	18	2.33	1	18	11	52
L64N 50+75W	.2	4	ND	9	29	18	2.40	1	18	11	59
L64N 51+00W	.1	4	ND	8	32	23	2.83	ND	23	14	121
L64N 51+25W	.1	5	ND	9	27	21	2.46	ND	19	12	74
L64N 51+50W	.2	3	10	12	37	50	3.08	ND	28	14	53
L64N 51+75W	.3	ND	ND	7	25	17	2.02	1	13	9	45
L64N 52+00W	.2	3	ND	6	25	17	2.08	ND	11	10	45
L64N 52+25W	.2	6	ND	6	21	11	1.76	1	10	8	46
L64N 52+50W	.4	4	ND	5	20	10	1.77	1	9	10	38
L64N 52+75W	.4	5	ND	6	25	15	1.83	ND	10	11	35
L64N 53+00W	.2	ND	ND	5	19	10	1.57	ND	8	8	58
L64N 53+25W	.3	ND	ND	10	33	24	2.37	1	21	10	39
L64N 53+50W	.3	8	ND	9	27	38	1.97	1	16	14	32
L64N 53+75W	.3	5	10	8	26	14	2.34	1	16	12	57
L64N 54+00W	.1	ND	5	5	7	66	1.63	1	4	45	95
L64N 54+25W	.1	4	ND	7	14	24	1.91	1	13	27	132
L64N 54+50W	.1	ND	ND	9	20	41	2.18	ND	21	26	111
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

VANGEOCHEM LAB LIMITED

MAIN OFFICE: 1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604) 986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604) 251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -= NOT ANALYZED, *AU= GEOCHEM

COMPANY: E&B EXPLORATIONS
 ATTENTION: L.SALEKEN & M.TINDALL
 PROJECT: 5061-CB PO# 5546

REPORT#: 860375PA
 JOB#: 860375
 INVOICE#: 860375NA

DATE RECEIVED: 86/08/18
 DATE COMPLETED: 86/08/26
 COPY SENT TO: VANC.OFFICE

ANALYST _____

PAGE 1 OF 13

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CD PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L52N 34+00W	.1	6	15	16	49	43	4.56	5	46	21	140
L52N 34+25W	.4	6	10	8	30	13	2.14	4	19	14	72
L52N 34+50W	.3	7	ND	6	27	8	1.98	ND	16	14	75
L52N 34+75W	.6	7	ND	8	26	10	1.92	1	13	15	66
L52N 35+00W	.8	10	ND	7	33	15	2.01	ND	21	17	66
L52N 35+25W	.3	8	ND	6	23	11	1.61	2	12	12	49
L52N 35+50W	.2	7	ND	9	27	13	2.06	1	16	13	61
L52N 35+75W	.1	5	ND	5	23	10	1.85	1	11	10	42
L52N 36+00W	.5	8	ND	6	27	11	1.84	1	14	15	48
L52N 36+25W	.1	5	ND	9	31	19	2.44	1	22	14	56
L52N 36+50W	.1	ND	ND	5	26	9	1.94	1	10	10	62
L52N 36+75W	.1	3	ND	7	24	8	1.77	2	9	8	72
L52N 37+00W	.1	3	15	10	39	21	2.70	1	24	12	78
L52N 37+25W	.1	5	ND	6	28	8	2.05	1	12	12	72
L52N 37+50W	.1	4	10	8	31	15	2.31	ND	18	14	67
L52N 37+75W	.1	3	5	8	29	15	2.35	1	18	12	51
L52N 38+00W	.1	5	15	9	32	18	2.52	2	19	12	45
L52N 38+25W	.1	ND	15	10	35	22	2.61	1	23	11	58
L52N 38+75W	.1	5	10	10	37	25	2.87	ND	23	13	62
L52N 39+00W	.1	6	15	10	33	19	2.50	2	25	13	54
L52N 39+25W	.1	3	10	7	29	21	2.30	ND	29	10	48
L52N 39+50W	.1	6	10	8	27	18	2.22	1	21	14	47
L52N 39+75W	.1	4	10	10	35	29	2.67	2	26	14	71
L52N 40+00W	.1	4	10	13	27	22	2.27	3	19	15	49
L52N 40+25W	.1	7	10	7	26	19	2.31	2	18	11	47
L52N 40+50W	.1	5	10	7	23	14	2.01	3	16	12	51
L52N 40+75W	.2	7	10	5	22	13	2.05	1	12	12	41
L52N 41+00W	.1	5	10	7	21	12	2.02	2	13	12	52
L52N 41+25W	.2	6	10	6	24	12	1.94	ND	14	11	49
L52N 41+50W	.3	5	5	5	24	10	1.84	ND	10	13	50
L52N 41+75W	.1	5	20	3	29	17	2.12	ND	17	10	59
L52N 42+00W	.1	8	ND	6	25	11	2.00	ND	11	12	54
L52N 42+25W	.1	6	ND	8	26	15	2.48	ND	16	14	48
L52N 42+50W	.2	5	ND	7	38	16	2.17	ND	17	12	47
L52N 42+75W	.1	4	ND	8	35	16	2.20	ND	20	13	57
L52N 43+00W	.3	8	10	7	39	13	2.20	ND	18	14	56
L52N 43+25W	.2	6	10	7	26	17	2.27	ND	15	13	40
L52N 43+50W	.1	5	ND	7	35	16	2.08	ND	16	12	50
L52N 43+75W	.1	4	ND	8	28	22	2.27	3	18	11	40
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

PROFILE
 AUG 27 1986
 SUBMIT

For Simpson

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CG PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L52N 44+00W	.1	8	ND	9	36	20	2.82	1	23	12	62
L52N 44+25W	.1	12	ND	10	28	19	2.79	3	16	14	59
L52N 44+50W	.2	3	ND	9	36	20	3.02	2	21	14	65
L52N 44+75W	.2	7	ND	11	32	25	2.85	1	20	14	54
L56N 34+00W	.1	9	ND	9	30	20	2.36	1	23	14	44
L56N 34+25W	.1	8	ND	6	27	15	2.14	ND	20	12	51
L56N 34+50W	.2	8	ND	ND	2	5	.15	1	2	9	36
L56N 34+75W	.6	3	ND	13	45	63	3.16	2	49	22	119
L56N 35+00W	.1	6	ND	ND	1	2	.06	ND	ND	2	27
L56N 35+25W	.1	5	ND	ND	4	18	.28	ND	6	5	14
L56N 35+50W	.1	9	ND	2	11	50	.84	ND	18	7	34
L56N 35+75W	.1	6	ND	ND	1	5	.10	1	1	2	21
L56N 36+00W	.3	8	ND	11	31	68	2.50	ND	31	15	65
L56N 36+25W	.7	8	ND	12	38	58	2.96	1	37	16	82
L56N 36+50W	.7	ND	ND	19	63	110	4.68	ND	68	29	128
L56N 36+75W	.8	9	ND	5	21	9	1.67	ND	8	11	38
L56N 37+00W	.5	9	ND	8	28	15	2.08	1	18	14	53
L56N 37+25W	.2	4	ND	10	31	21	2.22	ND	18	14	77
L56N 37+50W	.2	9	ND	8	24	14	1.76	2	12	13	47
L56N 37+75W	.4	7	ND	7	23	15	1.89	ND	21	13	41
L56N 38+00W	.1	5	ND	8	26	24	2.16	1	22	10	45
L56N 38+25W	.2	6	5	13	19	17	1.60	ND	17	13	52
L56N 38+50W	.1	4	ND	12	34	37	2.53	ND	30	14	63
L56N 38+75W	.3	8	ND	12	34	52	2.53	ND	36	17	87
L56N 39+00W	.4	7	ND	6	21	12	2.27	ND	11	14	45
L56N 39+25W	.2	6	ND	8	29	16	2.33	2	17	12	56
L56N 39+50W	.4	7	15	7	28	14	2.43	ND	17	16	58
L56N 39+75W	.2	4	ND	7	30	11	2.09	ND	16	14	73
L56N 40+00W	.4	5	20	5	24	7	1.51	ND	8	13	37
L56N 40+25W	.3	ND	ND	18	61	126	4.52	ND	65	26	116
L56N 40+50W	.3	4	ND	5	19	8	1.47	2	9	12	40
L56N 40+75W	.2	5	ND	9	27	27	2.26	1	22	15	60
L56N 41+00W	.1	4	ND	6	19	7	1.54	2	9	10	49
L56N 41+25W	.1	4	ND	5	17	6	1.27	ND	5	11	29
L56N 41+50W	.1	5	ND	8	27	18	2.42	ND	20	15	90
L56N 41+75W	.2	ND	ND	9	36	13	2.33	3	20	15	91
L56N 42+00W	.5	6	ND	5	22	9	1.86	1	12	14	55
L56N 42+25W	.1	ND	ND	6	16	7	1.73	ND	6	12	74
L56N 42+50W	.2	7	ND	4	18	5	1.24	2	5	10	31
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L56N 42+75W	.3	7	ND	5	25	8	1.55	1	11	9	61
L56N 43+00W	.3	7	ND	8	29	20	2.16	1	22	12	55
L56N 43+25W	.1	3	ND	10	30	19	2.05	ND	22	11	68
L56N 43+50W	.3	6	ND	2	7	32	.80	3	15	9	32
L56N 43+75W	.6	7	ND	14	41	87	3.08	1	49	19	110
L56N 44+00W	.1	6	ND	15	39	27	2.86	2	28	15	123
L56N 44+25W	.1	7	ND	10	25	26	1.92	ND	21	10	69
L56N 44+50W	.1	7	ND	7	28	19	2.41	5	19	9	48
L56N 44+75W	.1	6	ND	8	26	23	2.13	2	18	8	45
L56N 45+00W	.1	5	ND	6	26	9	2.00	ND	13	6	55
L56N 45+25W	.1	3	ND	2	15	4	1.06	2	5	3	18
L56N 45+50W	.1	ND	ND	4	21	9	1.90	1	11	4	44
L56N 45+75W	.1	6	ND	6	23	17	2.15	1	17	8	41
L56N 46+00W	.1	4	ND	6	23	15	2.18	ND	12	8	55
L56N 46+50W	.1	5	ND	8	28	50	2.26	2	20	9	60
L56N 46+75W	.1	6	ND	2	12	8	1.17	ND	3	8	24
L56N 47+00W	.3	7	ND	11	34	69	2.68	ND	29	17	70
L56N 47+25W	.1	6	ND	10	34	20	2.77	2	24	12	89
L56N 47+50W	.4	8	ND	7	18	29	2.08	1	12	19	73
L56N 47+75W	.2	8	ND	16	36	113	3.02	1	49	21	74
L56N 48+00W	.2	7	ND	5	21	12	2.03	2	12	9	59
L56N 48+25W	.1	5	ND	4	21	8	1.87	1	6	9	28
L56N 48+50W	.1	4	ND	9	37	24	3.29	3	25	13	83
L56N 48+75W	.1	8	5	7	26	21	2.80	3	15	11	40
L56N 49+00W	.1	ND	ND	5	50	10	2.13	ND	13	6	32
L56N 49+25W	.1	11	ND	10	31	28	3.05	ND	22	12	42
L56N 49+50W	.1	8	ND	8	25	20	2.55	ND	17	11	45
L56N 49+75W	.1	5	10	6	27	14	2.45	1	10	8	43
L58N 30+00W	.1	6	ND	8	24	16	1.84	ND	17	11	38
L58N 30+25W	.3	10	ND	7	24	12	2.16	4	17	14	50
L58N 30+50W	.1	5	ND	6	31	18	1.99	ND	17	10	49
L58N 30+75W	.1	5	ND	7	29	32	2.30	1	24	12	44
L58N 31+00W	.1	6	ND	6	26	19	1.88	1	19	11	36
L58N 31+25W	.1	4	ND	7	24	14	1.97	1	19	9	41
L58N 31+50W	.1	7	ND	9	35	26	2.64	ND	27	14	54
L58N 31+75W	.5	9	ND	6	22	11	1.67	1	15	14	50
L58N 32+00W	.4	6	5	11	38	44	3.12	3	36	18	57
L58N 32+25W	.2	7	30	7	23	12	1.82	2	18	10	36
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	0	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L58N 33+50W	.1	ND	ND	6	21	10	1.67	1	20	9	45
L58N 32+75W	.1	ND	ND	8	21	11	1.67	1	17	10	43
L58N 33+00W	.1	7	ND	5	21	13	1.82	1	15	12	39
L58N 33+25W	.1	4	ND	9	29	27	2.31	ND	26	13	45
L58N 34+00W	.1	5	ND	6	21	11	1.88	ND	19	23	48
L58N 34+25W	.1	6	ND	9	25	15	2.09	1	23	16	66
L58N 34+50W	.1	5	ND	5	20	9	1.65	ND	14	16	61
L58N 34+75W	.2	4	ND	5	20	10	1.65	ND	14	17	61
L58N 35+00W	.1	7	ND	5	20	9	1.64	ND	16	15	59
L58N 35+25W	.1	6	ND	7	24	14	1.81	ND	19	15	45
L58N 35+50W	.1	7	ND	7	24	14	1.83	ND	18	16	45
L58N 35+75W	.2	7	ND	5	21	8	1.64	ND	17	14	45
L58N 36+00W	.1	7	ND	7	25	16	1.90	ND	18	14	50
L58N 36+25W	.3	8	ND	6	22	15	1.97	2	19	16	41
L58N 36+75W	.2	5	20	12	19	48	2.69	2	20	18	103
L58N 37+00W	.1	5	ND	6	21	13	1.84	2	17	14	51
L58N 36+50W	.2	7	ND	6	21	14	1.94	1	16	15	41
L58N 37+25W	.2	7	ND	6	17	17	1.80	4	15	14	43
L58N 37+50W	.1	10	ND	6	18	16	1.81	3	14	13	46
L58N 37+75W	.1	6	ND	9	25	21	2.31	1	22	17	55
L58N 38+00W	.3	9	ND	6	18	11	1.86	1	12	14	34
L58N 38+25W	.1	6	ND	6	19	13	1.83	ND	21	13	34
L58N 39+00W	.2	ND	ND	5	20	8	1.69	1	15	12	52
L58N 39+25W	.1	7	ND	9	29	25	2.39	ND	25	14	40
L58N 39+50W	.1	7	ND	8	29	20	2.36	3	24	13	48
L58N 39+75W	.1	6	ND	8	27	19	2.29	ND	23	13	50
L58N 40+00W	.1	8	ND	11	37	28	2.74	2	28	17	57
L58N 40+25W	.1	7	ND	10	36	23	2.27	1	28	15	52
L58N 40+50W	.2	6	ND	10	37	23	2.33	ND	33	16	53
L58N 40+75W	.2	6	ND	5	24	14	1.74	2	14	12	36
L58N 41+00W	.5	8	ND	6	20	14	1.62	1	13	16	33
L58N 41+25W	.4	7	ND	6	22	9	1.64	1	15	15	61
L58N 41+50W	.4	7	ND	8	22	12	2.17	1	17	19	63
L58N 41+75W	.2	8	ND	7	23	13	2.22	1	18	15	65
L58N 42+00W	.1	4	ND	6	26	7	1.45	1	13	10	34
L58N 42+25W	.1	3	ND	6	22	8	1.33	3	9	10	50
L58N 42+50W	.1	4	20	10	34	19	2.49	ND	28	17	81
L58N 42+75W	.1	7	30	10	34	19	2.52	1	27	18	83
L58N 43+00W	.2	5	ND	6	21	16	1.52	1	16	13	46
L58N 43+25W	.3	4	ND	8	24	14	2.06	3	19	15	54
DETECTION LIMIT	.1	3	<E	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L58N 43+50W	.1	10	ND	7	26	14	2.24	1	20	9	57
L58N 43+75W	.2	5	ND	10	39	33	2.66	1	28	14	65
L58N 44+00W	.2	5	ND	9	39	31	2.56	1	26	15	61
L58N 44+25W	.3	7	ND	6	30	14	1.77	1	16	10	42
L58N 44+50W	.2	4	ND	5	24	12	1.97	1	14	10	41
L58N 44+75W	.2	4	ND	6	24	13	1.91	ND	15	9	41
L58N 45+00W	.2	5	ND	5	24	14	1.92	1	15	12	33
L58N 45+25W	.2	4	ND	6	21	11	1.72	1	14	10	37
L58N 45+50W	.4	ND	ND	6	23	12	1.98	ND	13	12	48
L58N 45+75W	.2	4	ND	7	23	14	1.97	1	14	13	87
L58N 46+00W	.2	3	ND	6	23	10	1.82	ND	15	11	47
L58N 46+25W	.2	ND	ND	6	22	14	1.86	1	14	11	111
L58N 46+50W	.1	4	ND	9	21	21	2.18	ND	17	14	77
L58N 46+75W	.2	6	ND	7	23	10	1.92	ND	15	12	53
L58N 47+00W	.1	ND	ND	7	25	14	2.13	ND	17	12	51
L58N 47+25W	.2	5	ND	7	23	17	1.87	ND	19	12	51
L58N 47+50W	.1	4	ND	7	21	9	1.57	1	13	13	70
L58N 47+75W	.2	7	ND	5	21	10	1.82	1	13	12	46
L58N 48+00W	.1	4	ND	9	28	12	2.47	1	18	12	50
L58N 48+25W	.1	4	ND	8	25	10	2.20	1	16	10	45
L58N 48+50W	.1	ND	ND	10	32	34	2.86	1	40	16	72
L58N 48+75W	.1	ND	ND	9	27	21	2.58	1	30	14	72
L58N 49+00W	.1	ND	ND	12	28	43	3.13	ND	30	16	99
L58N 49+25W	.1	6	15	10	29	24	2.68	ND	23	12	52
L58N 49+50W	.1	ND	ND	6	24	13	2.15	1	13	13	36
L58N 49+75W	.1	ND	ND	8	26	14	2.45	1	18	13	62
L86N 35+00W	.1	7	5	11	25	24	2.67	1	17	14	74
L86N 35+25W	.3	3	ND	12	24	25	2.75	2	14	11	74
L86N 35+50W	.3	5	ND	6	23	19	2.08	1	10	13	55
L86N 35+75W	.1	5	10	9	27	156	2.50	2	15	13	44
L86N 36+00W	.1	3	5	8	25	16	2.40	1	13	13	64
L86N 36+25W	.9	4	25	28	36	1771	3.33	5	27	18	75
L86N 36+50W	.4	6	10	8	22	91	2.36	2	12	13	51
L86N 36+75W	.3	8	45	11	23	309	2.56	3	13	13	80
L86N 37+00W	1.1	7	25	51	36	2086	4.17	8	29	28	105
L86N 37+25W	.4	ND	30	41	31	1647	4.25	8	31	21	132
L86N 37+50W	.5	4	20	18	44	1806	3.83	6	35	20	86
L86N 38+00W	.5	4	20	12	27	2755	2.54	4	26	16	69
L86N 38+50W	.3	4	10	7	30	98	2.62	2	16	14	58
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
LB6N 38+75W	.3	10	ND	6	23	13	2.08	ND	12	9	36
LB6N 39+00W	.4	9	10	6	21	66	2.77	1	12	11	49
LB6N 39+25W	.2	8	10	8	25	83	2.37	1	18	10	41
LB6N 39+50W	.6	8	40	12	29	1231	3.74	4	18	17	63
LB6N 39+75W	.4	13	160	19	17	994	4.69	4	11	21	104
LB6N 40+00W	.3	12	85	11	22	1060	3.34	4	14	16	54
LB6N 40+25W	1.7	7	445	9	20	503	4.74	2	10	16	66
LB6N 40+50W	.5	10	50	14	29	1703	4.19	7	22	22	94
LB6N 40+75W	.1	8	10	8	34	84	2.12	1	20	9	63
LB6N 41+00W	.2	9	5	7	36	30	2.25	1	19	10	75
LB6N 41+25W	.1	8	25	9	30	81	3.34	2	21	14	69
LB6N 41+50W	.2	7	5	8	28	41	2.95	1	20	14	74
LB6N 41+75W	.5	5	20	7	27	35	2.43	1	15	11	71
LB6N 42+00W	.3	14	15	6	19	58	2.79	4	10	13	40
LB6N 42+25W	.5	9	20	9	15	124	2.58	6	6	13	86
LB6N 42+50W	.1	10	20	11	23	36	2.91	3	15	14	137
LB6N 42+75W	.1	5	15	11	27	63	3.27	2	19	14	176
LB6N 43+00W	.3	11	10	7	25	63	3.18	7	10	10	35
LB6N 44+00W	.4	7	15	6	19	32	2.27	1	9	12	38
LB6N 44+25W	.7	11	15	6	21	97	2.59	2	10	14	36
LB6N 44+50W	.5	10	25	14	25	332	3.52	3	34	18	80
LB6N 44+75W	.5	10	20	6	16	25	2.08	1	12	12	31
LB6N 45+00W	.3	9	20	8	24	54	2.66	2	17	13	42
LB6N 45+25W	.3	5	20	10	23	54	3.12	2	17	16	86
LB6N 45+50W	1.1	15	25	6	12	34	3.83	11	5	20	63
LB6N 45+75W	.9	11	15	5	8	19	3.84	5	5	24	55
LB6N 46+00W	.3	12	20	7	22	21	3.12	2	12	19	58
LB6N 46+25W	.4	10	10	10	30	51	3.75	2	25	23	126
LB6N 46+50W	1.1	10	15	8	23	38	2.72	1	13	17	123
LB6N 46+75W	.2	12	10	9	24	41	2.79	1	21	19	115
LB6N 47+00W	.6	11	10	6	18	53	2.54	2	9	21	139
LB6N 47+25W	.4	9	ND	9	27	55	3.52	1	21	22	160
LB6N 47+50W	1.1	10	30	9	20	165	4.04	3	11	30	148
LB6N 47+75W	.5	11	20	12	31	265	3.25	2	28	22	117
LB6N 48+00W	.6	10	10	7	16	59	2.84	2	7	20	73
LB6N 48+25W	.7	22	15	23	90	170	5.07	3	99	32	327
LB6N 48+50W	.3	10	10	12	30	39	3.00	1	30	21	257
LB6N 48+75W	.3	16	35	14	34	47	4.07	4	27	28	257
LB6N 49+00W	.1	8	10	10	24	19	2.59	1	15	17	159
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU #PPB	CO PPM	CR PPM	CU PPM	FE I	MO PPM	NI PPM	PB PPM	ZN PPM
L86N 49+25W	.1	5	25	6	14	29	1.68	1	3	6	65
L86N 49+50W	.1	8	10	11	26	48	2.99	1	20	15	165
L86N 49+75W	.1	8	ND	12	31	85	3.17	1	22	16	261
L86N 50+00W	.1	9	10	13	25	112	2.42	1	13	11	285
L88N 35+00W	.1	8	10	11	23	133	2.41	1	23	13	55
L88N 35+25W	.1	ND	10	7	25	19	2.21	ND	17	6	79
L88N 35+50W	.1	6	5	16	37	106	3.33	1	25	19	91
L88N 35+75W	.1	4	5	18	35	75	3.24	1	26	16	86
L88N 36+00W	.3	5	15	6	30	17	2.44	1	5	9	44
L88N 36+25W	.2	5	5	6	34	25	3.02	1	10	11	59
L88N 36+50W	.1	5	5	6	25	27	2.14	ND	10	7	44
L88N 36+75W	.5	6	20	10	28	27	2.76	1	6	11	87
L88N 37+00W	.1	7	15	9	23	25	2.07	2	9	8	53
L88N 37+25W	.1	5	5	ND	2	9	.14	1	ND	1	11
L88N 37+50W	.3	8	15	7	26	41	2.35	1	13	10	46
L88N 37+75W	.6	6	15	8	27	53	2.94	1	9	11	67
L88N 38+00W	.3	8	20	6	25	44	2.17	1	10	8	44
L88N 38+25W	.5	6	ND	7	22	51	2.56	1	9	12	51
L88N 38+50W	.3	6	10	11	31	74	2.62	2	14	12	50
L88N 38+75W	.1	7	10	8	28	84	3.01	2	18	12	93
L88N 39+00W	.1	5	10	6	23	60	2.15	1	11	10	72
L88N 39+25W	.3	8	30	7	28	66	3.04	1	12	12	68
L88N 39+50W	.1	7	35	12	33	178	3.57	1	23	13	111
L88N 39+75W	.1	6	40	10	31	148	3.62	1	20	12	104
L88N 40+00W	.1	7	10	6	20	46	2.04	1	6	13	42
L88N 40+25W	.1	3	10	7	27	19	2.31	1	13	11	62
L88N 40+50W	.1	7	10	7	29	22	2.74	1	16	14	57
L88N 40+75W	.2	4	10	6	26	30	2.39	1	13	12	68
L88N 41+00W	.2	5	15	7	30	36	3.52	2	15	16	51
L88N 41+25W	.6	7	30	10	35	71	3.14	4	14	14	91
L88N 41+50W	.2	10	50	11	31	129	3.34	3	19	17	62
L88N 41+75W	.3	7	5	4	16	21	1.90	1	4	8	32
L88N 42+00W	.3	10	15	7	25	195	2.43	8	10	11	41
L88N 42+25W	.3	8	15	7	16	146	2.53	3	8	10	45
L88N 42+50W	.6	19	45	9	19	178	4.38	5	10	13	56
L88N 42+75W	.4	6	55	4	20	17	1.84	1	2	10	23
L88N 43+00W	.8	9	10	6	34	15	1.83	1	16	11	62
L88N 43+25W	.4	9	15	6	29	23	2.33	1	13	10	44
L88N 43+50W	.1	5	20	5	20	126	2.05	2	6	7	27
DETECTION LIMIT	.1	3	45	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L88N 43+75W	.1	4	5	4	22	19	1.53	ND	9	13	31
L88N 44+00W	.1	4	30	6	21	33	2.07	ND	9	12	52
L88N 44+25W	.1	6	5	7	31	60	2.74	ND	17	15	65
L88N 44+50W	.1	8	15	5	22	50	2.10	1	10	14	40
L88N 44+75W	.1	5	10	9	32	109	2.76	1	19	19	66
L88N 45+00W	.1	9	30	13	28	594	3.27	3	19	17	42
L88N 45+25W	.1	8	10	11	26	104	2.94	1	20	21	60
L88N 45+50W	.1	4	10	9	20	72	3.00	1	12	18	105
L88N 45+75W	.1	3	ND	3	14	19	1.84	ND	3	11	18
L88N 46+00W	.1	8	35	11	28	264	3.36	5	15	20	92
L88N 46+25W	.1	8	15	4	17	51	2.37	2	4	15	32
L88N 46+50W	.1	5	10	4	15	45	2.13	2	6	15	44
L88N 46+75W	.5	7	10	10	22	95	2.81	1	14	19	136
L88N 47+00W	.1	6	5	4	15	32	1.56	ND	6	14	44
L88N 47+25W	.1	5	ND	5	19	26	2.09	ND	9	14	52
L88N 47+50W	.1	8	20	6	21	36	2.36	1	8	16	38
L88N 47+75W	.1	3	15	20	44	223	4.30	2	31	29	99
L88N 48+00W	.2	7	10	5	15	23	1.75	1	4	15	39
L88N 48+25W	.4	3	ND	2	8	13	.81	ND	5	11	46
L88N 48+50W	.4	7	25	7	26	46	2.97	2	24	14	101
L88N 48+75W	.2	7	5	9	20	24	2.31	1	12	15	149
L88N 49+00W	.3	9	15	16	29	108	3.74	2	20	25	146
L88N 49+25W	.4	7	10	13	25	103	2.89	18	14	27	157
L88N 49+50W	.1	ND	10	8	7	168	1.44	34	14	6	281
L88N 49+75W	.1	9	15	10	22	1221	2.60	8	14	18	92
L88N 50+00W	.2	3	ND	1	5	605	.47	2	9	5	19
L90N 35+00W	.1	5	ND	5	20	30	1.75	ND	7	13	40
L90N 35+25W	.1	5	5	11	29	32	2.96	ND	22	21	97
L90N 35+50W	.1	5	5	6	27	94	2.40	ND	12	15	41
L90N 35+75W	.1	4	5	10	33	109	2.68	ND	15	16	46
L90N 36+00W	.1	6	20	8	25	60	2.29	ND	12	17	50
L90N 36+25W	.3	5	5	7	24	25	2.38	ND	7	16	57
L90N 36+50W	.2	7	10	11	23	50	2.92	ND	11	17	117
L90N 36+75W	.2	7	20	10	29	46	3.58	1	14	22	105
L90N 37+00W	.5	6	15	10	28	45	2.78	1	18	19	127
L90N 37+25W	.1	7	5	7	25	32	2.55	ND	13	19	71
L90N 37+50W	.3	6	10	10	29	130	2.97	1	19	20	84
L90N 37+75W	.1	4	5	6	22	17	2.37	ND	8	15	54
L90N 38+00W	.2	5	15	9	24	85	3.43	1	12	23	72
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L90N 38+25W	.1	3	10	16	35	803	3.35	2	30	19	81
L90N 38+50W	.1	4	5	14	38	684	2.79	1	25	17	62
L90N 38+75W	.1	ND	10	18	40	1804	3.77	1	39	22	88
L90N 39+00W	.2	4	5	5	16	58	1.97	ND	6	9	47
L90N 39+25W	.3	3	15	6	20	76	2.54	ND	9	16	68
L90N 39+50W	.1	3	20	7	26	47	2.54	ND	11	11	58
L90N 39+75W	.1	4	10	7	25	28	2.54	ND	9	13	64
L90N 40+00W	.2	5	35	12	33	220	3.85	1	28	17	122
L90N 40+25W	.1	5	15	7	25	46	2.43	ND	10	13	54
L90N 40+50W	.2	3	5	5	22	37	2.13	ND	8	13	33
L90N 40+75W	.1	8	30	13	34	217	4.80	2	25	18	88
L90N 41+00W	.1	3	5	9	24	198	3.34	2	15	17	57
L90N 41+25W	.1	11	15	30	19	683	5.12	6	21	29	90
L90N 41+50W	.1	11	15	12	26	386	3.89	4	20	19	63
L90N 41+75W	.1	5	5	7	21	54	2.82	2	8	17	79
L90N 42+00W	.1	5	10	8	24	296	2.88	6	11	19	53
L90N 42+25W	.2	4	5	9	29	54	3.84	2	15	20	122
L90N 42+50W	.2	6	5	7	23	25	2.36	ND	9	16	59
L90N 42+75W	.8	4	20	28	72	2441	6.11	5	72	37	100
L90N 43+00W	.1	7	5	8	27	74	2.66	1	12	14	60
L90N 43+25W	.1	9	5	9	24	64	2.79	ND	24	16	58
L90N 43+50W	.2	11	10	11	22	84	3.44	1	17	20	69
L90N 43+75W	.2	7	ND	8	21	27	2.26	1	9	15	78
L90N 44+00W	.1	7	ND	6	22	272	2.23	1	10	14	65
L90N 44+25W	.3	5	5	19	48	2071	4.04	5	52	25	135
L90N 44+50W	.1	9	10	9	35	587	2.28	3	22	16	72
L90N 44+75W	.1	8	10	10	35	1269	2.82	4	21	23	47
L90N 45+00W	.2	8	10	6	23	89	2.05	1	12	16	39
L90N 45+25W	.1	11	5	17	45	1006	3.52	4	39	25	88
L90N 45+50W	.4	11	ND	17	55	113	3.66	2	38	19	149
L90N 45+75W	.1	7	10	11	33	658	2.79	3	19	19	53
L90N 46+00W	.1	9	5	9	39	60	2.87	ND	26	19	103
L90N 46+25W	.1	8	ND	7	31	51	2.70	1	16	18	71
L90N 46+50W	.1	10	ND	9	29	63	2.26	2	16	19	51
L90N 46+75W	.2	11	15	8	26	81	2.43	4	14	17	49
L90N 47+00W	.1	6	ND	8	25	201	2.10	2	22	20	56
L90N 47+25W	.1	10	10	11	29	221	1.76	2	19	21	51
L90N 47+50W	.1	7	5	9	32	374	1.90	2	23	23	45
L90N 47+75W	.1	10	10	8	21	144	1.94	2	14	19	47
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CD PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L90N 48+00W	.1	7	15	9	29	128	3.63	2	16	17	60
L90N 48+25W	.1	9	20	9	25	112	3.51	3	14	14	72
L90N 48+50W	.4	9	20	7	27	161	3.29	3	16	15	53
L90N 48+75W	.3	8	10	7	23	101	2.59	3	12	17	53
L90N 49+00W	.3	13	10	8	25	108	2.90	3	12	14	65
L90N 49+25W	.3	4	10	19	44	475	4.94	13	36	25	126
L90N 49+50W	.3	7	10	9	23	171	2.07	4	11	14	64
L90N 49+75W	.2	11	ND	31	38	415	5.32	21	24	23	86
L92N 36+00W	.3	5	10	13	44	34	4.37	1	28	18	100
L92N 36+25W	.5	6	ND	9	31	19	3.07	ND	16	13	106
L92N 36+50W	.1	6	ND	8	28	22	2.71	ND	15	14	68
L92N 36+75W	.7	8	5	12	20	29	3.97	1	9	16	134
L92N 37+00W	.8	6	ND	10	25	45	2.95	2	11	16	124
L92N 37+50W	.1	5	ND	11	28	337	2.57	2	19	12	53
L92N 37+75W	.2	7	ND	12	37	229	3.33	2	21	13	56
L92N 38+00W	.1	8	ND	10	36	337	3.27	2	19	13	65
L92N 38+25W	.1	8	ND	9	30	204	2.72	1	14	13	49
L92N 38+50W	.2	4	ND	12	37	97	3.65	2	22	15	98
L92N 38+75W	.4	9	ND	11	35	51	3.49	2	18	16	64
L92N 39+00W	.6	6	ND	10	26	113	3.46	2	18	17	83
L92N 39+25W	.4	8	ND	8	28	33	2.99	1	15	13	63
L92N 39+50W	.2	6	ND	6	24	27	2.28	ND	8	10	45
L92N 39+75W	.2	4	5	11	28	219	2.74	1	14	13	64
L92N 40+00W	.3	6	15	5	24	50	2.22	1	9	11	66
L92N 40+25W	.6	5	25	4	22	40	1.84	1	5	8	59
L92N 40+50W	.2	5	5	15	50	149	3.68	1	47	16	129
L92N 41+25W	.1	7	5	9	31	142	2.93	1	14	13	122
L92N 42+25W	.3	6	ND	13	34	1218	2.35	2	16	12	99
L92N 42+50W	.6	3	ND	6	28	38	3.11	1	14	13	94
L92N 42+75W	.1	7	ND	9	32	76	3.22	ND	23	14	77
L92N 43+00W	.2	7	ND	6	22	25	2.01	1	10	11	45
L92N 43+25W	.2	ND	ND	6	22	25	2.33	ND	9	10	43
L92N 43+50W	.2	3	ND	4	22	25	2.29	ND	9	11	46
L92N 43+75W	.3	4	10	7	32	530	3.41	2	17	20	57
L92N 44+00W	.1	4	5	6	26	44	2.92	1	13	16	65
L92N 44+25W	.2	4	5	7	28	57	2.63	1	14	14	55
L92N 44+50W	.2	4	ND	8	30	83	3.09	1	14	16	62
L92N 44+75W	.5	6	15	7	25	92	2.79	1	14	14	68
L92N 45+00W	.1	5	15	14	32	243	2.96	1	23	15	48
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CD PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L92N 46+00W	.1	4	5	5	26	155	2.20	3	11	20	35
L92N 46+75W	.1	6	10	15	31	135	2.90	4	21	14	37
L92N 47+00W	.1	6	ND	6	27	44	2.17	3	11	13	65
L92N 48+75W	.2	7	5	9	27	58	2.68	1	13	12	84
L92N 49+00W	.3	6	ND	10	31	71	2.35	1	12	13	100
L92N 49+25W	.2	7	10	16	50	480	3.07	3	30	16	97
L94N 36+00W	.1	8	ND	11	35	36	3.15	1	23	14	61
L94N 36+25W	.1	6	ND	11	36	32	3.33	ND	26	14	63
L94N 36+50W	.1	5	ND	11	37	52	3.35	1	23	18	64
L94N 36+75W	.2	4	ND	11	38	185	3.67	2	22	17	95
L94N 37+00W	.2	6	ND	13	40	46	3.56	1	22	20	86
L94N 37+25W	.2	5	ND	10	34	37	3.22	1	19	15	76
L94N 37+50W	.1	6	ND	6	26	32	2.64	3	12	12	54
L94N 37+75W	.2	7	ND	15	38	175	3.37	2	22	18	88
L94N 38+00W	.2	3	ND	11	28	31	2.80	ND	9	13	94
L94N 38+50W	.1	6	ND	11	37	41	3.23	ND	21	13	65
L94N 38+75W	.2	4	ND	12	38	40	3.43	ND	22	16	74
L94N 39+00W	.1	5	ND	9	33	30	3.02	1	18	14	66
L94N 39+25W	.2	4	ND	9	35	54	2.91	1	17	15	67
L94N 39+50W	.2	8	ND	16	44	87	3.76	1	30	18	69
L94N 40+00W	.2	7	ND	9	32	186	2.70	2	23	12	86
L94N 40+25W	.2	4	ND	12	36	376	3.13	2	23	16	81
L94N 40+50W	.3	5	5	13	36	476	2.95	3	23	16	108
L94N 40+75W	.2	5	ND	12	35	169	3.09	2	21	15	81
L94N 41+00W	.3	6	ND	12	34	59	3.46	2	18	19	110
L94N 41+25W	.3	5	10	14	38	67	3.85	2	21	20	123
L94N 41+50W	.3	7	ND	9	30	57	3.19	2	15	21	123
L94N 41+75W	.2	5	ND	10	30	57	3.06	2	16	16	90
L94N 42+00W	.5	3	5	11	36	33	3.16	2	18	15	196
L94N 42+25W	.2	9	ND	9	29	142	2.95	6	16	15	70
L94N 42+50W	.3	7	ND	6	25	48	2.93	4	11	16	106
L94N 42+75W	.2	7	ND	8	28	578	2.75	3	12	16	87
L94N 43+00W	.1	7	ND	4	20	25	2.10	1	7	10	55
L94N 43+25W	.1	6	ND	2	13	12	1.37	ND	1	9	30
L94N 43+50W	.1	8	ND	8	29	26	2.98	1	15	31	65
L94N 43+75W	.1	9	ND	5	23	17	2.18	1	8	10	49
L94N 44+00W	.1	6	ND	4	19	12	1.78	1	5	12	44
L94N 44+25W	.1	5	ND	10	33	44	2.97	1	21	13	51
L94N 44+50W	.1	7	ND	7	26	33	2.46	1	14	14	53
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPH	AS PPH	AU #PPB	CD PPH	CR PPH	CU PPH	FE %	MO PPH	NI PPH	PB PPH	ZN PPH
L94N 44+75W	.1	4	5	6	24	26	2.42	1	13	9	74
L94N 45+00W	.1	4	10	11	30	70	3.02	2	23	12	64
L94N 45+25W	.4	5	ND	7	27	112	2.68	3	15	13	65
L94N 45+50W	.2	6	5	10	26	122	2.79	2	16	12	57
L94N 45+75W	.4	4	ND	5	23	68	2.26	3	10	11	38
L94N 46+25W	.8	5	10	9	23	908	2.44	4	13	14	41
L94N 46+50W	.3	7	ND	8	30	55	3.11	2	17	15	54
L94N 46+75W	.6	6	ND	6	19	56	2.03	1	10	14	44
L94N 47+00W	.7	6	ND	5	20	19	1.96	1	7	11	39
L94N 47+25W	.5	6	10	8	29	185	3.18	1	17	17	52
L94N 47+50W	.6	6	ND	6	24	34	2.43	1	12	12	64
L94N 47+75W	.6	7	5	11	22	96	2.93	1	17	19	83
L94N 48+00W	.6	9	5	15	22	121	3.75	1	15	33	138
L94N 48+25W	.7	9	25	11	30	81	3.10	1	19	17	73
L94N 48+50W	.7	9	ND	10	22	90	3.09	2	12	19	81
L94N 48+75W	.7	9	20	13	32	215	3.24	1	21	20	83
L94N 49+00W	1.1	ND	20	21	60	1960	5.25	5	54	33	126
L94N 49+25W	.8	6	10	16	42	975	3.78	3	32	23	79
L94N 49+50W	.7	9	10	11	23	64	2.92	1	13	18	160
L94N 49+75W	.8	6	ND	10	25	60	2.61	2	11	15	79
L96N 36+00W	.5	7	ND	18	56	87	4.07	1	56	19	65
L96N 36+25W	.6	5	ND	8	30	41	2.55	1	16	15	44
L96N 36+50W	.6	4	ND	7	30	17	2.72	1	9	13	63
L96N 36+75W	.5	8	ND	11	33	21	2.99	ND	18	14	67
L96N 37+00W	.6	7	ND	6	28	12	2.47	ND	10	12	63
L96N 37+25W	.4	9	ND	18	49	74	3.86	ND	43	18	69
L96N 37+50W	.5	5	ND	11	38	32	3.17	ND	24	15	61
L96N 37+75W	.8	4	ND	22	62	2031	5.43	5	54	34	131
L96N 38+00W	.5	3	ND	12	36	38	3.09	1	26	16	75
L96N 38+25W	.6	7	ND	10	28	33	3.05	1	18	20	89
L96N 38+50W	.3	ND	ND	9	30	39	3.03	1	17	18	76
L96N 38+75W	.5	8	ND	19	112	46	4.11	1	112	17	67
L96N 39+00W	.8	9	ND	11	36	77	3.18	2	20	17	61
L96N 39+25W	.6	8	ND	15	33	41	3.21	1	20	19	144
L96N 39+50W	.5	8	ND	12	38	39	3.54	ND	28	19	95
L96N 39+75W	.6	7	ND	14	33	51	3.15	1	23	19	81
L96N 40+00W	.4	7	ND	11	35	45	3.23	1	26	19	75
L96N 40+25W	.4	7	ND	11	28	35	2.93	1	19	19	63
L96N 40+50W	.3	6	ND	11	27	33	2.21	1	16	15	43
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE Z	MO PPM	NI PPM	PB PPM	ZN PPM
L96N 40+75W	.1	6	10	12	30	53	2.97	ND	26	19	71
L96N 41+00W	.1	9	5	7	24	7	1.40	ND	11	17	69
L96N 41+25W	.3	ND	5	6	24	16	2.24	ND	18	14	67
L96N 41+50W	.1	ND	5	7	26	18	2.28	ND	18	15	103
L96N 41+75W	.3	6	5	7	24	16	2.20	ND	16	14	89
L96N 42+00W	.4	4	10	8	19	34	1.82	ND	12	13	53
L96N 42+25W	.1	4	10	13	28	50	2.68	ND	17	16	77
L96N 42+50W	.1	6	10	13	34	88	3.06	1	26	18	89
L96N 42+75W	.5	9	5	4	20	19	1.88	ND	6	16	30
L96N 43+00W	.4	8	5	7	23	13	2.12	ND	9	13	50
L96N 43+25W	.2	7	ND	8	25	17	2.48	ND	14	15	105
L96N 43+50W	.4	5	ND	6	22	12	2.11	ND	13	14	150
L96N 43+75W	.4	6	ND	6	25	17	2.47	ND	16	16	190
L96N 44+00W	.5	6	ND	7	22	20	2.00	1	14	14	128
L96N 44+25W	.6	6	10	9	22	27	2.44	ND	15	16	183
L96N 44+50W	.3	9	10	12	34	77	3.23	1	26	22	135
L96N 44+75W	.7	7	15	5	22	24	2.35	1	11	15	115
L96N 45+00W	.5	8	10	14	27	124	3.08	3	19	33	278
L96N 45+25W	.6	8	ND	13	24	174	3.30	3	19	36	413
L96N 45+50W	.5	9	ND	7	23	20	2.40	1	17	17	180
L96N 45+75W	.5	9	10	5	17	382	1.22	4	16	12	36
L96N 46+00W	.5	7	5	3	11	333	.74	3	14	11	26
L96N 46+50W	.6	9	ND	3	17	13	1.59	1	6	11	30
L96N 46+75W	1.9	13	5	5	12	22	1.24	1	11	16	57
L96N 47+00W	.7	7	25	6	23	59	2.70	1	15	20	77
L96N 47+25W	.6	7	ND	4	15	13	1.47	1	6	9	40
L96N 47+50W	.6	8	ND	5	16	17	1.94	1	11	14	73
L96N 47+75W	.6	8	ND	7	22	42	2.49	1	16	17	77
L96N 48+00W	.3	8	ND	4	18	14	1.83	ND	11	12	72
L96N 48+25W	.4	9	5	8	23	60	2.72	1	18	18	103
L96N 48+50W	.3	11	ND	7	24	49	3.03	1	18	17	105
L96N 48+75W	.4	9	10	8	25	69	2.62	ND	18	16	64
L96N 49+00W	.4	9	ND	7	23	29	2.53	ND	17	17	82
L96N 49+25W	.3	11	15	8	23	217	2.75	ND	17	25	67
L96N 49+50W	.4	6	ND	3	13	9	1.48	ND	4	9	29
L96N 49+75W	.3	8	ND	6	18	38	2.26	ND	8	14	62
L96N 50+00W	.2	13	15	9	22	53	2.60	ND	15	18	79
L56N 46+25W	.1	9	ND	6	20	12	1.87	ND	13	11	46
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPH	AS PPH	AU *PPB	CO PPH	CR PPH	CU PPH	FE I	MO PPH	NI PPH	PB PPH	ZN PPH
L74N 39+50W	.1	ND	ND	6	20	21	2.12	1	15	10	99
L74N 39+75W	ND	ND	ND	5	21	17	1.63	ND	14	7	39
L74N 40+00W	.1	ND	ND	6	24	15	1.83	ND	18	11	41
L74N 40+25W	.1	ND	ND	6	24	14	1.81	ND	16	11	41
L74N 40+50W	.2	ND	ND	9	26	19	2.39	ND	23	10	53
L74N 40+75W	.1	ND	ND	9	30	21	2.63	ND	25	10	62
L74N 41+00W	.3	ND	ND	10	32	43	2.20	ND	24	11	71
L74N 41+50W	.3	ND	ND	7	32	26	1.91	ND	24	11	59
L74N 41+75W	.2	ND	ND	8	34	23	2.10	1	24	10	80
L74N 42+00W	.2	ND	ND	8	33	22	2.05	ND	24	11	78
L74N 42+25W	.2	ND	ND	7	25	15	2.19	ND	18	10	56
L74N 42+50W	.2	4	ND	6	26	13	2.09	ND	17	10	59
L74N 42+75W	.3	3	ND	9	27	18	2.37	1	21	13	47
L74N 43+00W	.3	5	ND	9	27	19	2.38	1	21	11	46
L74N 43+25W	.5	3	ND	6	22	9	1.67	1	15	9	42
L74N 43+50W	.4	ND	ND	11	28	17	2.92	1	17	13	159
L74N 43+75W	.5	ND	ND	9	29	20	2.72	ND	22	13	75
L74N 44+00W	.3	ND	ND	7	26	14	2.17	ND	15	8	59
L74N 44+25W	.2	3	ND	5	23	9	1.74	ND	13	8	50
L74N 44+50W	.3	5	ND	5	23	8	1.70	ND	14	10	51
L74N 44+75W	.5	4	ND	4	20	9	1.44	1	17	11	45
L74N 45+00W	.3	ND	ND	10	31	22	2.11	ND	24	11	82
L74N 45+25W	.2	ND	ND	9	32	18	2.42	1	23	13	86
L74N 45+50W	.1	ND	ND	8	27	13	1.73	1	14	9	61
L74N 45+75W	.2	4	ND	7	27	18	1.88	ND	21	11	49
L74N 46+00W	.2	ND	ND	8	30	19	2.21	ND	20	12	58
L74N 46+25W	.1	ND	ND	6	26	10	1.87	1	16	10	49
L74N 46+50W	.3	3	ND	9	36	18	2.44	1	24	10	75
L74N 46+75W	.2	ND	ND	7	31	15	2.17	1	18	10	61
L74N 47+00W	.1	ND	ND	12	35	42	2.93	1	32	12	69
L74N 47+25W	.2	3	ND	8	30	17	2.57	1	22	13	55
L74N 47+50W	.3	ND	ND	11	32	18	2.91	1	26	12	63
L74N 47+75W	.2	6	ND	6	22	10	1.58	1	12	10	45
L74N 48+00W	.5	5	ND	6	27	10	2.51	1	17	12	46
L74N 48+25W	.2	ND	ND	5	24	8	2.11	1	12	11	43
L74N 48+50W	.4	5	ND	6	25	11	2.08	ND	14	12	52
L74N 48+75W	.6	ND	ND	9	33	22	2.29	1	22	12	69
L74N 49+00W	.6	4	ND	6	26	15	2.14	1	17	12	46
L74N 49+25W	.5	ND	ND	8	34	26	2.64	1	27	13	53
DETECTION LIMIT	.1	3	45	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE I	MO PPM	NI PPM	PS PPM	ZN PPM
L74N 49+50W	.1	ND	ND	3	17	6	1.38	1	7	9	30
L74N 49+75W	.1	ND	ND	6	28	30	1.85	1	22	11	50
L74N 50+00W	.1	ND	ND	6	25	18	1.59	1	15	10	45
L74N 50+25W	.1	3	ND	9	39	34	2.30	1	26	13	66
L74N 50+50W	.1	ND	ND	6	25	20	1.70	1	17	11	56
L74N 50+75W	.1	ND	ND	7	30	17	1.91	1	19	9	60
L74N 51+00W	.1	ND	ND	10	36	29	2.54	1	26	10	91
L74N 51+25W	.1	ND	ND	9	33	26	2.34	1	22	10	79
L74N 51+50W	.1	5	ND	17	44	76	3.38	1	41	21	85
L74N 51+75W	.2	5	ND	11	36	39	2.71	1	23	18	43
L74N 52+00W	.1	5	ND	16	46	60	3.38	1	39	19	49
L78N 35+00W	.2	6	15	24	28	84	2.95	6	19	16	74
L78N 35+25W	.6	ND	ND	21	22	320	3.88	6	19	23	107
L78N 35+50W	.5	3	ND	13	24	292	3.19	3	18	19	99
L78N 35+75W	.1	4	ND	6	21	16	2.07	1	10	13	88
L78N 36+00W	.2	5	ND	10	28	24	2.65	1	17	14	85
L78N 36+25W	.1	ND	ND	8	26	20	2.69	1	13	14	96
L78N 36+50W	.6	5	10	30	38	145	4.81	1	19	21	160
L78N 36+75W	.2	ND	ND	10	25	51	2.67	1	17	16	103
L78N 37+00W	.1	ND	ND	11	34	94	3.46	1	24	19	97
L78N 37+25W	.2	ND	ND	14	37	62	3.74	2	38	23	140
L78N 37+50W	.1	5	ND	11	30	98	2.92	1	21	17	75
L78N 37+75W	.2	5	ND	12	28	42	2.82	2	19	15	98
L78N 38+00W	.3	7	ND	12	24	30	2.65	2	16	15	105
L78N 38+25W	.3	8	ND	9	24	32	2.29	1	15	16	74
L78N 38+50W	.2	6	ND	8	28	30	2.28	1	18	16	53
L78N 38+75W	.2	4	ND	8	26	26	2.28	1	20	15	53
L78N 39+00W	.3	7	ND	7	22	20	1.81	1	15	14	47
L78N 39+25W	.2	8	ND	6	20	16	1.73	1	14	13	49
L78N 39+50W	.2	7	ND	8	21	19	1.89	1	14	11	47
L78N 39+75W	.2	5	ND	8	23	17	2.10	1	16	13	45
L78N 40+00W	.2	5	ND	8	25	18	2.04	1	17	15	44
L78N 40+25W	.2	6	ND	8	25	19	2.10	1	15	15	53
L78N 40+50W	.2	6	ND	7	24	21	1.85	1	16	14	55
L78N 40+75W	.2	7	ND	9	28	19	2.00	1	15	14	66
L78N 41+00W	.2	7	ND	9	27	19	1.90	1	15	13	63
L78N 41+25W	.2	ND	ND	14	48	102	3.58	2	50	21	85
L78N 41+50W	.2	8	ND	10	36	41	2.40	1	24	16	72
L78N 41+75W	.2	4	ND	9	31	43	2.19	1	21	15	88
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CD PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L68N 56+00W	.1	4	ND	9	35	30	2.81	1	28	14	59
L68N 56+25W	.2	9	20	6	23	17	2.08	1	19	12	39
L68N 56+50W	.9	7	10	5	14	17	1.14	1	13	12	21
L68N 56+75W	.4	9	10	7	24	22	1.85	3	19	13	32
L68N 57+00W	.1	9	ND	7	25	27	2.09	ND	18	12	45
L68N 57+25W	.1	7	20	8	34	31	2.36	2	23	13	49
L68N 57+50W	.1	7	ND	8	32	24	2.65	2	22	14	90
L68N 57+75W	.1	6	ND	6	20	21	1.86	ND	15	13	53
L68N 58+00W	.1	5	ND	6	24	15	2.05	ND	16	12	67
L68N 58+25W	.1	3	ND	4	14	8	1.51	ND	7	13	50
L68N 58+50W	.1	6	20	6	17	24	1.94	3	13	12	49
L68N 58+75W	.1	4	ND	5	18	17	2.03	ND	15	12	65
L68N 59+00W	.1	7	15	4	17	14	1.72	ND	10	12	40
L68N 59+25W	.2	5	5	5	18	25	1.94	ND	13	14	36
L68N 59+50W	.2	5	5	5	14	11	1.54	ND	8	11	53
L68N 59+75W	.1	7	10	9	20	43	2.12	ND	19	27	79
L68N 60+00W	.3	8	10	5	14	15	1.60	2	9	14	42
L70N 50+75W	.3	5	10	10	33	23	2.29	2	24	15	68
L70N 51+00W	.5	ND	5	8	31	16	2.20	2	19	14	61
L70N 51+25W	.3	3	5	9	31	18	3.17	1	19	16	118
L70N 51+50W	.4	8	ND	5	23	16	2.26	3	21	13	39
L70N 51+75W	.2	4	ND	5	18	12	1.73	ND	11	10	36
L70N 52+00W	.2	6	ND	7	26	19	2.37	ND	20	14	49
L70N 52+25W	.2	4	ND	9	26	25	2.78	2	26	16	54
L70N 52+50W	.1	6	ND	8	26	23	2.70	ND	24	16	58
L70N 52+75W	.2	7	ND	7	26	20	2.81	2	15	17	74
L70N 53+00W	.2	8	15	7	25	24	2.42	1	17	15	60
L70N 53+25W	.4	6	ND	7	36	16	2.66	1	20	14	51
L70N 53+50W	.3	5	20	6	27	16	2.49	ND	19	14	54
L70N 53+75W	.1	ND	ND	6	22	11	2.02	ND	14	11	70
L70N 54+00W	.3	6	ND	8	33	23	2.85	2	25	15	110
L70N 54+25W	.3	7	10	7	35	27	2.65	2	24	15	61
L70N 54+50W	.3	3	ND	12	50	95	3.68	2	39	19	110
L70N 54+75W	.2	5	5	15	49	84	3.84	2	35	21	122
L70N 55+25W	.1	4	ND	14	55	110	4.34	2	57	22	66
L70N 55+50W	.2	5	10	10	32	42	2.59	1	30	16	47
L70N 55+75W	.3	7	5	9	31	65	2.40	2	26	16	33
L70N 56+00W	.2	5	ND	10	36	30	2.73	2	27	16	38
L70N 56+25W	.1	7	10	6	24	20	2.12	ND	16	13	67
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU +PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L78N 42+00W	.1	7	ND	10	30	28	2.58	1	26	12	58
L78N 42+25W	.1	8	ND	8	26	22	2.04	ND	17	8	65
L78N 42+50W	.1	5	ND	8	27	23	2.10	1	20	8	64
L78N 42+75W	.1	6	ND	10	38	36	2.36	1	23	7	85
L78N 43+25W	.1	6	ND	9	37	132	2.48	5	25	8	86
L78N 43+50W	.1	5	ND	9	38	126	2.49	5	26	8	88
L78N 43+75W	.2	3	ND	14	53	421	3.32	4	33	11	116
L78N 44+00W	.1	7	ND	8	26	75	2.13	2	15	8	41
L78N 44+25W	.1	4	ND	13	34	130	2.13	2	18	9	104
L78N 44+50W	.1	4	ND	12	41	340	3.29	4	30	13	83
L78N 44+75W	.1	7	ND	13	35	235	3.22	4	25	12	74
L78N 45+00W	.3	9	ND	9	23	116	2.12	4	15	11	52
L78N 45+25W	.1	5	ND	9	25	27	2.25	1	15	12	92
L78N 45+50W	.8	7	ND	9	22	20	2.00	1	12	14	105
L78N 45+75W	.8	7	10	7	20	99	2.14	1	13	13	80
L78N 46+00W	1.1	8	ND	9	23	24	1.87	1	14	15	113
L78N 46+25W	1.1	7	ND	8	24	25	2.03	1	17	17	66
L78N 46+50W	1.0	8	85	9	29	25	2.69	1	21	17	74
L78N 46+75W	1.2	9	ND	5	22	9	2.32	1	10	17	55
L78N 47+00W	1.0	8	ND	9	31	22	2.76	1	25	17	69
L78N 47+25W	.7	8	ND	9	30	29	2.85	1	33	16	73
L78N 47+50W	.9	10	ND	8	26	22	2.50	1	20	15	62
L78N 47+75W	1.2	14	ND	6	21	11	2.03	1	13	15	48
L78N 48+00W	1.1	10	ND	10	26	22	2.64	1	17	15	75
L78N 48+25W	1.0	11	ND	9	34	15	2.54	1	21	15	61
L78N 48+50W	.9	8	ND	8	33	14	2.43	1	20	13	60
L78N 48+75W	.8	9	ND	6	26	13	1.51	1	14	13	41
L78N 49+00W	.8	8	ND	7	30	22	2.92	1	19	16	50
L78N 49+25W	.8	9	ND	4	19	9	1.80	1	10	13	36
L78N 49+50W	.2	6	ND	9	36	44	3.52	ND	28	16	78
L78N 49+75W	.1	4	ND	8	24	22	2.71	ND	19	10	87
L78N 50+00W	.1	8	ND	7	27	24	2.29	ND	18	8	52
L78N 50+25W	.6	8	ND	6	18	32	1.67	1	12	10	47
L78N 50+50W	1.0	6	ND	8	26	29	2.83	1	15	16	96
L78N 51+50W	1.0	6	ND	13	25	80	2.61	2	22	17	102
L78N 51+75W	1.2	10	ND	11	32	54	2.91	2	23	17	91
L78N 52+00W	1.2	9	ND	11	33	36	2.58	2	22	16	93
L78N 52+25W	1.1	9	ND	8	35	25	2.40	1	26	21	69
L78N 52+50W	1.1	4	ND	9	26	19	2.17	1	20	18	68
DETECTION LIMIT	.1	3	+5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPH	AS PPH	AU #PPB	CO PPH	CR PPH	CU PPH	FE %	MO PPH	NI PPH	PB PPH	ZN PPH
L78N 54+00W	.5	9	ND	7	20	11	1.80	1	13	14	66
L78N 54+25W	.2	11	ND	5	23	9	2.35	ND	14	15	90
L78N 54+50W	.1	7	ND	5	24	17	2.23	ND	16	13	49
L78N 54+75W	.1	8	ND	5	23	18	2.17	ND	16	14	46
L78N 55+00W	.1	6	ND	8	26	25	2.33	ND	20	14	56
L78N 55+25W	.2	11	ND	9	29	27	2.44	ND	23	14	58
L78N 55+50W	.1	6	ND	5	29	11	2.12	ND	14	12	66
L78N 55+75W	.1	12	ND	9	26	35	2.47	1	20	14	37
L78N 56+00W	.2	8	ND	6	42	12	2.26	1	26	18	56
L80N 35+00W	.2	7	ND	8	37	22	2.21	1	27	14	71
L80N 35+25W	.1	8	ND	7	25	15	2.32	ND	14	14	56
L80N 35+50W	.1	7	ND	9	29	20	2.59	ND	17	15	84
L80N 35+75W	.3	15	ND	12	33	46	3.00	1	29	17	70
L80N 36+00W	.2	8	ND	6	25	14	2.01	1	13	16	45
L80N 36+25W	.1	8	ND	6	25	15	2.29	ND	13	15	47
L80N 36+50W	.5	ND	ND	22	56	72	4.56	1	50	31	102
L80N 36+75W	.8	ND	5	16	58	113	4.53	1	53	25	96
L80N 37+50W	.1	7	ND	4	22	12	1.93	ND	11	14	39
L80N 37+75W	.2	9	5	3	18	7	1.60	ND	6	14	30
L80N 38+00W	.2	7	ND	8	24	53	2.14	1	22	15	50
L80N 38+25W	.1	6	ND	4	16	8	1.73	ND	9	9	51
L80N 38+50W	.1	7	ND	5	16	13	1.89	ND	12	8	52
L80N 38+75W	.1	4	ND	8	19	17	2.14	ND	13	9	90
L80N 39+00W	.1	7	ND	5	22	12	2.29	ND	9	7	57
L80N 39+25W	.1	3	ND	5	23	12	2.16	ND	9	5	57
L80N 39+50W	.1	4	ND	16	42	75	3.62	1	33	15	62
L80N 39+75W	.1	6	ND	11	24	27	2.38	ND	15	11	58
L80N 40+00W	.1	7	ND	7	20	23	2.05	ND	12	12	58
L80N 40+25W	.1	11	ND	6	18	17	1.88	ND	8	12	38
L80N 40+50W	.1	6	ND	6	18	36	1.77	ND	13	11	41
L80N 40+75W	.1	4	ND	4	18	14	2.00	ND	11	7	47
L80N 41+00W	.1	4	ND	5	20	17	2.29	ND	13	8	51
L80N 41+25W	.1	ND	ND	9	28	50	2.69	ND	19	8	55
L80N 41+50W	.1	3	ND	8	24	52	2.18	ND	16	7	49
L80N 41+75W	.1	8	ND	8	26	36	2.11	ND	14	12	52
L80N 42+00W	.1	4	ND	8	25	39	2.10	1	16	14	47
L80N 42+25W	.1	7	ND	6	23	30	1.96	1	13	13	55
L80N 42+50W	.1	7	ND	7	26	44	2.28	ND	14	13	69
L80N 42+75W	.1	11	ND	23	35	173	3.08	1	24	22	70
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPH	AS PPH	AU +PPB	CD PPH	CR PPH	CU PPH	FE Z	MO PPH	NI PPH	PB PPH	ZN PPH
LBON 43+00W	.6	7	ND	9	27	120	2.01	1	19	11	81
LBON 43+25W	.6	6	ND	11	29	275	2.50	1	19	14	252
LBON 43+50W	.7	6	ND	9	27	72	2.26	2	13	10	226
LBON 43+75W	.9	5	ND	13	38	51	2.87	1	27	15	285
LBON 44+00W	.9	7	ND	6	23	34	2.17	3	13	13	137
LBON 44+25W	1.0	5	ND	12	41	31	2.36	2	23	14	259
LBON 44+50W	.9	6	ND	9	28	86	2.13	1	17	15	151
LBON 44+75W	.9	10	ND	11	27	159	2.02	4	17	14	84
LBON 45+00W	.9	3	ND	11	29	47	2.37	1	18	14	180
LBON 45+25W	1.2	8	ND	12	26	50	2.32	6	13	16	125
LBON 45+50W	1.0	9	ND	9	24	52	1.80	2	14	11	65
LBON 46+00W	.8	5	ND	8	21	19	1.87	ND	13	9	82
LBON 46+25W	.9	6	ND	7	24	22	1.78	1	14	8	49
LBON 46+50W	.9	5	ND	8	25	36	1.81	1	13	10	55
LBON 46+75W	1.0	3	ND	8	24	62	2.05	1	16	10	50
LBON 47+00W	.9	7	ND	8	21	42	1.87	ND	14	11	33
LBON 47+25W	.7	3	ND	8	22	51	1.76	ND	13	9	45
LBON 47+50W	.6	4	ND	7	22	23	1.95	ND	14	8	35
LBON 47+75W	.6	5	ND	6	20	35	1.69	ND	12	9	47
LBON 48+00W	.9	5	ND	8	20	40	1.75	1	11	11	55
LBON 48+50W	.6	6	ND	9	23	54	1.54	1	20	10	59
LBON 48+75W	1.0	8	ND	4	18	11	1.33	1	9	11	56
LBON 49+00W	1.1	7	ND	4	17	12	1.55	1	9	12	40
LBON 49+25W	1.0	5	ND	6	21	22	1.77	1	12	10	57
LBON 49+50W	.7	4	ND	8	22	12	1.98	1	13	10	67
LBON 49+75W	1.0	ND	5	12	25	29	2.45	1	15	14	96
LBON 50+00BL	1.4	6	ND	22	10	97	3.57	ND	10	12	121
LBON 50+25W	.5	3	ND	12	34	79	3.04	ND	25	10	55
LBON 50+50W	.6	5	ND	6	23	27	1.85	1	12	8	28
LBON 50+75W	.4	ND	ND	7	19	21	1.80	ND	12	7	61
LBON 51+00W	.5	4	ND	8	18	25	1.58	1	10	6	41
LBON 51+25W	.8	ND	ND	5	17	26	1.51	1	8	8	35
LBON 51+50W	.8	4	ND	10	30	57	2.32	1	20	11	53
LBON 51+75W	.8	ND	ND	11	26	40	2.29	1	18	10	58
LBON 52+00W	.8	5	ND	10	34	59	2.65	1	25	11	57
LBON 52+25W	.6	3	ND	8	23	19	1.89	1	14	9	44
LBON 52+50W	.8	3	ND	5	21	17	1.90	ND	13	9	84
LBON 52+75W	.8	7	ND	8	21	17	1.90	ND	14	9	75
LBON 53+00W	.8	5	ND	4	16	16	1.71	1	9	10	35
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPH	AS PPH	AU PPB	CO PPH	CR PPH	CU PPH	FE %	MO PPH	NI PPH	PB PPH	ZN PPH
L80N 53+75W	ND	4	ND	4	21	12	1.86	1	10	6	53
L80N 54+00W	.2	3	ND	6	26	18	2.53	1	19	12	69
L80N 54+25W	.2	ND	ND	6	25	20	2.27	1	14	27	53
L80N 54+50W	.4	3	ND	9	30	20	2.76	1	16	14	108
L80N 54+75W	ND	7	ND	5	23	9	2.22	1	13	10	60
L80N 55+00W	ND	3	ND	7	24	12	2.18	1	13	11	66
L80N 55+25W	.1	3	ND	6	25	27	2.19	1	15	13	48
L80N 55+50W	.3	3	ND	9	32	45	2.27	1	24	16	74
L80N 55+75W	.3	3	ND	9	31	21	2.68	1	23	14	87
L80N 56+00W	.4	3	ND	13	39	36	2.95	1	36	15	60
L82N 35+00W	.2	3	ND	7	19	10	1.73	ND	9	11	40
L82N 35+25W	.3	4	ND	6	23	12	1.91	ND	13	10	49
L82N 35+50W	.4	6	ND	9	29	25	2.51	1	18	13	75
L82N 35+75W	.7	5	ND	8	24	18	2.14	1	13	14	84
L82N 36+00W	.7	5	ND	7	29	16	2.25	1	17	15	63
L82N 36+25W	.7	10	ND	8	29	20	2.29	1	18	13	65
L82N 36+50W	.6	7	ND	10	34	18	1.97	1	19	15	96
L82N 36+75W	.5	4	ND	8	28	14	2.28	1	16	12	57
L82N 37+00W	.6	8	ND	9	32	25	2.60	1	20	16	75
L82N 37+25W	.3	7	ND	10	29	23	2.65	1	24	12	71
L82N 37+50W	.6	3	ND	13	31	35	2.36	3	20	14	120
L82N 37+75W	.9	7	ND	11	22	35	3.07	3	14	12	104
L82N 38+00W	.3	5	ND	9	25	22	2.63	1	17	16	96
L82N 38+25W	.6	4	ND	6	26	13	2.43	1	13	15	49
L82N 38+50W	.7	7	ND	7	27	16	2.62	1	16	16	55
L82N 38+75W	.5	ND	ND	10	34	28	3.31	1	18	17	127
L82N 39+00W	.7	4	ND	10	33	26	3.22	2	18	18	121
L82N 39+25W	1.3	8	15	12	21	33	3.39	2	12	21	106
L82N 39+50W	1.0	12	ND	18	25	80	3.76	5	15	22	133
L82N 39+75W	.7	7	ND	8	20	16	2.31	1	12	15	90
L82N 40+00W	.7	7	ND	7	19	12	2.05	1	9	12	74
L82N 40+25W	.1	4	ND	10	27	25	2.66	1	21	13	86
L82N 40+50W	.7	7	ND	10	25	24	2.75	1	19	15	84
L82N 40+75W	.4	4	ND	11	26	53	3.20	1	15	14	92
L82N 41+00W	1.3	4	20	11	20	96	4.07	4	15	21	118
L82N 41+25W	.9	11	20	11	24	83	3.65	3	16	15	82
L82N 41+50W	.7	5	10	10	25	76	3.65	3	15	17	79
L82N 41+75W	.4	8	15	12	24	106	3.05	2	14	13	48
L82N 42+00W	.3	6	5	10	23	79	3.01	2	17	12	86
DETECTION LIMIT	.1	3	45	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU +PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NJ PPM	PB PPM	ZN PPM
LB2N 42+25W	.4	8	25	9	24	79	2.65	1	12	9	55
LB2N 42+50W	.4	4	15	11	22	43	2.42	1	9	6	75
LB2N 42+75W	.4	8	ND	8	23	44	2.30	ND	11	9	53
LB2N 43+00W	.5	3	ND	9	24	46	2.45	ND	10	8	59
LB2N 43+25W	.3	7	ND	5	19	15	1.84	ND	6	8	58
LB2N 43+50W	.4	4	ND	8	25	80	2.45	ND	10	11	225
LB2N 43+75W	.3	4	ND	8	28	67	2.59	1	14	10	135
LB2N 44+00W	.2	4	ND	7	25	64	2.36	1	13	9	114
LB2N 44+25W	.2	4	ND	8	28	63	2.61	1	16	17	286
LB2N 44+50W	.1	ND	ND	13	37	127	3.66	1	31	14	246
LB2N 44+75W	.1	ND	ND	9	24	25	2.67	ND	16	9	463
LB2N 45+00W	.1	ND	ND	11	30	34	3.03	ND	25	9	205
LB2N 45+25W	.1	4	10	10	22	60	2.59	1	13	18	237
LB2N 45+50W	.1	6	ND	8	25	29	2.53	ND	15	11	65
LB2N 45+75W	.1	ND	ND	12	41	50	2.51	ND	30	8	98
LB2N 46+00W	.2	5	ND	11	43	44	2.80	ND	31	9	114
LB2N 46+25W	.1	6	10	10	27	70	2.32	1	15	9	49
LB2N 46+50W	.2	3	ND	7	32	38	2.22	ND	17	8	79
LB2N 46+75W	.1	ND	ND	9	25	18	2.02	ND	13	8	103
LB2N 47+00W	.1	3	ND	9	30	46	2.59	ND	20	7	80
LB2N 47+25W	.1	ND	ND	13	38	39	2.32	ND	29	8	134
LB2N 47+50W	.1	5	ND	7	26	26	2.03	ND	16	7	74
LB2N 47+75W	.1	5	ND	8	29	33	2.27	ND	20	7	45
LB2N 48+00W	.1	ND	ND	7	25	56	2.08	ND	13	8	52
LB2N 48+25W	.2	ND	ND	8	29	34	2.19	ND	17	11	107
LB2N 48+50W	.1	ND	ND	8	22	21	2.31	ND	14	4	106
LB2N 48+75W	.2	5	ND	11	27	68	2.87	1	15	7	126
LB2N 49+00W	.1	7	10	9	23	53	2.42	1	12	7	124
LB2N 49+25W	.1	4	10	10	25	61	2.67	1	15	11	130
LB2N 49+50W	.1	6	10	9	22	43	2.32	ND	13	7	89
LB2N 49+75W	.1	5	5	9	20	24	2.00	ND	11	6	117
LB2N 50+25W	.1	4	10	15	22	32	2.77	ND	13	7	410
LB2N 50+50W	.1	3	ND	12	17	43	2.80	ND	9	7	202
LB2N 50+75W	.1	7	10	9	18	21	2.21	ND	7	6	105
LB2N 51+00W	.1	3	5	9	23	18	2.37	ND	13	7	208
LB2N 51+25W	.6	5	5	19	46	482	3.57	4	36	9	107
LB2N 52+00W	.1	3	5	6	20	14	1.79	ND	10	4	67
LB2N 52+25W	.1	ND	30	8	22	19	2.13	ND	13	5	123
LB2N 52+50W	.1	ND	5	7	21	12	1.87	ND	11	3	81
DETECTION LIMIT	.1	3	+5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPH	AS PPH	AU PPB	CO PPH	CR PPH	CU PPH	FE I	MO PPH	NI PPH	PB PPH	ZN PPH
LB2N 52+75W	.2	4	ND	5	20	10	1.77	ND	10	10	61
LB2N 53+00W	.4	ND	ND	8	23	28	2.11	ND	13	11	89
LB2N 53+25W	.4	4	ND	8	30	38	2.23	1	18	11	94
LB2N 53+50W	.4	4	ND	8	26	46	2.16	ND	16	8	55
LB2N 53+75W	.3	5	ND	8	30	19	2.44	ND	18	10	95
LB2N 54+00W	.4	ND	ND	9	27	46	2.21	1	14	10	74
LB2N 54+25W	.4	ND	ND	9	26	49	2.16	1	14	11	50
LB2N 54+50W	.3	7	ND	8	23	20	1.92	ND	14	10	60
LB2N 54+75W	.2	4	ND	8	25	25	2.04	1	14	10	53
LB2N 55+00W	.2	3	ND	7	23	20	1.97	ND	14	10	45
LB2N 55+25W	.1	ND	ND	9	24	24	2.48	ND	15	10	115
LB2N 55+50W	.3	4	ND	20	38	240	4.01	2	37	12	79
LB2N 55+75W	.1	ND	5	33	125	82	6.61	ND	58	7	85
LB2N 56+00W	.2	ND	5	31	236	70	5.57	1	102	7	80
LB4N 35+00W	.1	ND	ND	8	35	16	2.79	ND	19	9	112
LB4N 35+25W	.3	ND	ND	28	62	403	5.72	16	46	16	69
LB4N 35+50W	.2	4	ND	10	32	87	2.60	4	18	9	40
LB4N 35+75W	.3	ND	ND	10	35	246	2.75	4	23	11	45
LB4N 36+00W	.4	ND	5	16	45	611	3.61	4	35	10	66
LB4N 36+25W	.2	ND	5	17	36	320	3.58	3	30	9	76
LB4N 36+50W	.3	ND	ND	12	35	146	3.13	2	27	10	57
LB4N 36+75W	.2	ND	ND	8	39	22	2.42	ND	23	9	121
LB4N 37+00W	.1	ND	ND	12	46	40	3.21	1	35	7	70
LB4N 37+25W	.3	ND	ND	14	49	26	3.00	1	27	11	130
LB4N 37+50W	.2	ND	ND	12	41	43	3.09	2	31	8	74
LB4N 37+75W	.1	ND	ND	10	33	24	2.67	1	11	8	107
LB4N 38+00W	.2	ND	ND	10	27	62	2.75	2	19	8	73
LB4N 38+25W	.4	5	ND	9	34	35	2.80	ND	21	9	38
LB4N 38+50W	.8	5	ND	11	32	23	2.89	1	23	17	111
LB4N 38+75W	.8	3	ND	12	33	55	3.19	2	24	19	78
LB4N 39+00W	.6	4	20	14	37	55	3.33	1	34	17	113
LB4N 39+25W	.9	ND	ND	11	36	45	3.47	1	26	17	108
LB4N 39+50W	.8	ND	ND	13	33	32	3.28	1	24	16	88
LB4N 39+75W	.9	ND	ND	16	35	28	3.34	1	23	16	146
LB4N 40+00W	1.4	ND	ND	15	32	115	4.91	3	27	21	203
LB4N 40+25W	.8	3	ND	11	32	38	3.30	2	20	16	126
LB4N 40+50W	.7	ND	ND	16	37	46	3.98	4	28	17	215
LB4N 40+75W	.6	7	10	8	30	154	3.38	3	20	18	50
LB4N 41+00W	.9	ND	ND	8	24	40	3.15	2	15	18	68
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU +PPB	CO PPM	CR PPM	CU PPM	FE I	MO PPM	NI PPM	PB PPM	ZN PPM
LB4N 41+25W	.1	16	60	7	22	78	2.50	15	18	16	69
LB4N 41+50W	.1	11	10	13	27	94	4.16	2	21	14	129
LB4N 41+75W	.3	6	25	7	16	34	2.22	1	9	8	84
LB4N 42+00W	.4	8	5	7	21	25	2.47	1	12	6	99
LB4N 42+25W	.6	12	5	6	23	32	2.56	1	10	12	92
LB4N 42+50W	.6	6	ND	9	24	26	2.82	1	16	13	59
LB4N 42+75W	.6	4	15	11	30	123	2.91	1	23	13	74
LB4N 43+00W	.6	6	5	11	28	50	3.59	1	17	16	106
LB4N 43+25W	1.1	11	10	9	18	67	2.77	4	9	11	88
LB4N 43+50W	.9	10	10	6	14	34	2.24	1	6	10	62
LB4N 43+75W	.6	10	20	7	17	46	2.41	1	8	13	66
LB4N 44+00W	.5	8	ND	8	22	24	2.58	1	17	11	113
LB4N 44+25W	.8	9	15	8	16	48	3.72	2	8	16	107
LB4N 44+50W	.5	4	5	9	20	31	2.75	1	14	14	114
LB4N 44+75W	.1	ND	5	10	28	26	2.84	ND	21	11	76
LB4N 45+00W	.1	3	ND	6	23	22	2.63	1	16	11	92
LB4N 45+25W	.4	4	ND	8	24	37	2.49	ND	19	12	101
LB4N 45+50W	.6	5	5	7	22	34	2.36	1	16	9	162
LB4N 45+75W	.5	6	10	8	23	26	2.50	1	13	10	106
LB4N 46+00W	.2	9	10	10	25	38	3.07	1	21	10	122
LB4N 46+25W	.1	ND	ND	12	26	27	3.18	ND	28	9	166
LB4N 46+50W	.1	ND	ND	10	27	17	2.52	ND	20	6	158
LB4N 46+75W	.1	ND	ND	15	31	47	3.58	ND	30	11	167
LB4N 47+00W	.1	ND	10	14	39	53	4.30	1	31	22	179
LB4N 47+25W	.1	ND	ND	14	29	25	3.25	1	23	10	198
LB4N 47+50W	.3	ND	5	13	21	61	4.75	ND	18	13	215
LB4N 47+75W	.1	ND	35	21	24	25	3.12	1	22	10	273
LB4N 48+00W	.1	ND	ND	7	24	15	2.18	ND	11	6	156
LB4N 48+25W	.2	ND	ND	13	38	34	2.77	1	28	10	189
LB4N 48+50W	.2	3	ND	15	30	56	3.09	1	19	13	147
LB4N 48+75W	.1	ND	ND	14	34	75	3.09	1	27	12	133
LB4N 49+00W	.2	3	ND	9	29	22	2.27	1	18	11	90
LB4N 49+25W	.2	ND	5	13	32	63	3.65	1	29	12	327
LB4N 49+50W	.2	ND	5	14	27	46	3.27	1	17	13	200
LB4N 49+75W	1.1	9	10	15	21	54	4.83	3	11	17	304
LB4N 50+00W	.3	ND	5	12	28	50	3.11	ND	21	12	160
LB4N 50+25W	.5	3	5	9	30	24	2.54	1	18	13	114
LB4N 50+50W	1.5	13	ND	18	12	57	4.45	1	7	43	173
LB4N 50+75W	.8	4	5	11	23	29	2.97	1	13	15	103
DETECTION LIMIT	.1	3	+5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPH	AS PPH	AU PPH	CO PPH	CR PPH	CU PPH	FE I	MO PPH	NI PPH	PB PPH	ZN PPH
LB4N 51+00W	.4	5	ND	11	28	21	2.65	1	16	10	190
LB4N 51+25W	.4	ND	ND	15	38	55	3.64	1	29	9	158
LB4N 51+50W	.2	3	ND	13	32	23	2.75	ND	22	10	152
LB4N 51+75W	ND	ND	ND	15	30	64	3.77	1	18	15	166
LB4N 52+00W	.4	11	ND	18	12	53	4.60	1	7	25	151
LB4N 52+25W	.9	ND	ND	15	6	33	4.76	1	7	7	92
LB4N 52+50W	ND	ND	ND	9	24	25	2.60	1	11	6	98
LB4N 52+75W	ND	3	ND	12	33	27	2.82	ND	22	8	77
LB4N 53+00W	ND	3	ND	11	35	16	2.48	ND	19	8	187
LB4N 53+25W	ND	ND	ND	11	37	21	2.67	ND	27	7	176
LB4N 53+50W	ND	3	ND	11	28	43	2.78	ND	18	6	184
LB4N 53+75W	ND	ND	ND	12	38	52	3.00	1	32	14	116
LB4N 54+00W	.2	5	ND	13	28	43	3.09	1	19	12	183
LB4N 54+25W	.6	12	ND	16	23	101	2.87	1	16	16	237
LB4N 54+50W	1.0	7	ND	16	18	119	3.34	ND	9	12	313
LB4N 54+75W	.2	8	ND	11	24	31	2.92	ND	16	9	132
LB4N 55+00W	.4	6	ND	11	22	39	2.63	1	12	9	81
LB4N 55+25W	.2	4	ND	17	31	90	3.14	3	21	13	113
LB4N 55+50W	.4	ND	ND	29	59	329	6.52	33	64	15	143
LB4N 55+75W	.5	4	10	27	43	29	4.82	1	37	8	141
LB4N 56+00W	.3	6	25	13	39	24	3.23	1	31	11	73
LB4N 56+25W	.3	6	ND	11	29	29	2.85	ND	16	12	81
LB4N 56+50W	.6	9	ND	11	21	39	3.23	1	9	12	102
LB4N 56+75W	.4	5	15	14	29	48	3.94	1	15	12	166
LB4N 57+00W	.4	8	ND	9	25	19	2.40	ND	10	10	119
LB4N 57+25W	.2	8	25	14	23	106	3.33	1	13	11	101
LB4N 57+50W	.4	ND	ND	26	59	50	7.05	ND	34	5	150
LB4N 57+75W	.4	7	5	16	36	71	4.59	1	18	9	118
LB4N 58+00W	.1	11	ND	12	29	157	2.73	1	16	10	69
LB4N 58+25W	.2	8	ND	9	25	43	2.10	ND	13	10	53
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1



VANGEOCHEM LAB LIMITED

MAIN OFFICE
1521 PEMBERTON AVE.
NORTH VANCOUVER, B.C. V7P 2S3
(604) 986-5211 TELEX: 04-352578

BRANCH OFFICE
1630 PANDORA ST.
VANCOUVER, B.C. V5L 1L6
(604) 251-5656

----- GEOCHEMICAL ANALYTICAL REPORT -----

CLIENT: E & B EXPLORATIONS LIMITED
ADDRESS: 1440 - 800 W. Pender St.
: Vancouver B.C.
: V6C 2V6

DATE: Aug 12 1986

REPORT#: 8603506A
JOB#: 860350

PROJECT#: 5061 - CARIBOO BELL
SAMPLES ARRIVED: Aug 6 1986
REPORT COMPLETED: Aug 12 1986
ANALYSED FOR: Au (FA/AAS)

INVOICE#: 860350NA
TOTAL SAMPLES: 5
SAMPLE TYPE: 5 ROCK
REJECTS: SAVED

SAMPLES FROM: E & B EXPLORATIONS LIMITED
COPY SENT TO: E & B EXPLORATIONS LIMITED

PREPARED FOR: J. BELLAMY & L. SALEKEN

ANALYSED BY: VGC Staff

SIGNED: 

GENERAL REMARK: None



VANGEOCHEM LAB LIMITED

MAIN OFFICE
1521 PEMBERTON AVE.
NORTH VANCOUVER, B.C. V7P 2S3
(604) 986-5211 TELEX: 04-352578

BRANCH OFFICE
1630 PANDORA ST.
VANCOUVER, B.C. V5L 1L6
(604) 251-5656

REPORT NUMBER: 8603506A

JOB NUMBER: 860350

E & B EXPLORATIONS LIMITED

PAGE 1 OF 1

SAMPLE #	Au
MR 86-001	55
MR 86-002	45
MR 86-003	10
MR 86-004	160
MR 86-005	nd

DETECTION LIMIT

5

nd = none detected

-- = not analysed

is = insufficient sample

MAIN OFFICE: 1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604)986-5211 TELEX:04-352578
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND IS DILUTED TO 10 ML WITH WATER.
 THIS LEACH IS PARTIAL FOR SN, MN, FE, CA, P, CR, MG, BA, PD, AL, NA, K, W, PT AND SR. AU AND PD DETECTION IS 3 PPM.
 IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -- NOT ANALYZED

COMPANY: E&B EXPLORATIONS
 ATTENTION:
 PROJECT: 5061-CARIBOO BELL

REPORT#: 860350PA
 JOB#: 860350
 INVOICE#: 860350NA

DATE RECEIVED: 86/08/06
 DATE COMPLETED: 86/08/08
 COPY SENT TO:

ANALYST W. R. R.

SAMPLE NAME	AG PPM	AL %	AS PPM	AU PPM	BA PPM	BI PPM	CA %	CD PPM	CO PPM	CR PPM	CU PPM	FE %	K %	MG %	MN PPM	MO PPM	NA %	NI PPM	P %	PB PPM	PD PPM	PT PPM	SB PPM	SN PPM	SR PPM	U PPM	W PPM	ZN PPM
MR 86-001	.7	1.30	25	ND	29	5	.68	.1	14	31	52	4.34	.10	1.06	467	2	.01	12	.15	13	ND	ND	3	1	74	ND	ND	44
MR 86-002	.8	1.28	22	ND	31	ND	.71	.1	8	21	64	3.33	.10	.93	589	4	.01	4	.15	12	ND	ND	3	2	117	ND	ND	66
MR 86-003	.8	1.45	25	ND	26	4	.96	.8	16	30	154	3.73	.10	1.39	906	3	.01	11	.17	22	ND	ND	ND	ND	101	ND	ND	158
MR 86-004	.8	1.95	12	ND	32	ND	.77	.3	11	13	129	3.75	.17	1.09	736	ND	.01	6	.14	6	ND	ND	ND	ND	106	ND	ND	55
MR 86-005	.2	.19	12	ND	34	ND	3.58	.1	20	41	117	4.21	.17	1.54	1433	ND	.01	20	.11	26	ND	ND	3	3	497	ND	ND	53
DETECTION LIMIT	.1	.01	3	3	1	3	.01	.1	1	1	1	.01	.01	.01	1	1	.01	1	.01	2	3	5	2	2	1	5	3	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L52N 48+00W	.2	5	10	10	30	31	2.41	1	20	11	68
L52N 48+25W	.1	7	10	10	34	31	2.33	2	24	9	64
L52N 48+50W	.2	ND	ND	8	34	26	1.79	2	22	13	50
L52N 48+75W	.2	7	ND	6	30	13	2.10	1	15	9	83
L52N 49+00W	.2	7	ND	8	37	11	2.29	1	16	8	86
L52N 49+25W	.2	4	ND	7	33	18	2.42	1	20	10	47
L52N 49+50W	.2	7	ND	8	31	16	2.46	2	20	12	34
L52N 49+75W	.2	ND	ND	15	49	63	3.84	2	42	17	51
L52N 50+00W	.2	9	ND	8	41	18	2.77	3	20	11	41
L52N 51+25W	.3	7	ND	5	25	10	2.30	3	11	11	34
L52N 51+50W	.2	5	ND	8	30	20	2.93	2	19	13	54
L54N 34+00W	.3	ND	ND	8	30	22	2.37	1	19	9	68
L54N 34+25W	.2	4	ND	9	35	30	2.44	1	24	9	47
L54N 34+50W	.4	5	ND	9	35	30	2.38	2	22	11	48
L54N 34+75W	.2	3	ND	7	31	26	2.39	1	21	9	44
L54N 35+00W	.1	ND	ND	8	32	27	2.53	1	21	8	48
L54N 35+75W	.2	ND	ND	8	30	15	2.22	ND	17	8	62
L54N 36+00W	.3	ND	ND	9	33	25	2.29	2	23	9	71
L54N 36+50W	.3	4	ND	9	37	25	2.47	1	24	9	50
L54N 36+75W	.4	4	ND	10	40	24	2.69	2	31	9	70
L54N 37+00W	.4	4	ND	10	38	22	2.70	1	26	11	68
L54N 37+25W	.3	4	ND	11	40	36	2.88	2	35	10	52
L54N 37+50W	.4	7	ND	9	35	17	2.34	1	21	12	71
L54N 37+75W	.4	ND	ND	9	36	19	2.40	1	23	10	68
L54N 38+00W	.7	7	ND	8	27	15	2.15	2	21	12	49
L54N 38+25W	.5	9	ND	7	26	14	2.13	2	19	10	49
L54N 38+50W	.5	5	ND	6	24	12	1.82	2	15	10	45
L54N 38+75W	.3	4	ND	6	26	12	1.97	2	15	10	41
L54N 39+00W	.5	3	ND	6	25	12	2.01	1	16	10	45
L54N 39+25W	.5	6	ND	6	25	13	1.97	1	16	11	51
L54N 39+50W	.4	4	ND	6	22	13	1.62	2	12	13	38
L54N 39+75W	.3	6	10	3	20	7	1.52	1	7	9	24
L54N 40+00W	.4	3	ND	7	28	11	2.04	ND	13	10	50
L54N 40+50W	.3	7	10	8	26	8	2.16	2	13	9	68
L54N 40+75W	.3	ND	ND	9	34	19	2.53	1	23	9	60
L54N 41+00W	.4	4	ND	6	30	14	2.22	1	18	10	54
L54N 41+25W	.4	ND	10	9	34	22	2.45	ND	23	11	57
L54N 41+50W	.4	ND	10	11	38	18	2.82	1	33	10	112
L54N 41+75W	.4	ND	ND	11	36	16	2.73	1	31	11	111
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L54N 51+75W	.1	3	ND	6	43	11	1.75	1	17	9	61
L54N 52+00W	.3	3	ND	7	27	22	2.10	ND	16	13	57
L54N 52+25W	.3	4	ND	11	43	25	2.49	1	27	12	72
L54N 52+50W	.3	5	ND	10	34	26	2.34	ND	24	13	56
L54N 52+75W	.2	3	10	8	24	26	2.43	ND	17	15	95
L54N 53+00W	.1	ND	ND	9	29	17	2.30	ND	18	14	79
L54N 53+25W	.2	ND	5	11	43	49	2.75	ND	30	17	68
L54N 53+50W	.1	4	10	8	34	18	2.62	ND	19	14	77
L54N 53+75W	.1	ND	15	9	36	17	2.66	ND	21	13	74
L54N 54+00W	.3	ND	ND	5	23	8	1.63	ND	10	11	68
L56N 50+00W	.5	5	ND	9	30	16	2.58	1	16	14	52
L56N 50+25W	.4	ND	ND	5	25	14	2.03	1	10	13	39
L56N 50+50W	.4	7	10	16	43	114	3.20	1	32	20	66
L56N 50+75W	.3	6	10	7	26	13	2.22	ND	14	9	46
L56N 51+00W	.4	5	10	8	30	13	2.54	ND	14	11	74
L56N 51+25W	.3	ND	10	9	34	12	2.42	ND	16	12	76
L56N 51+50W	.5	ND	10	9	37	19	2.78	1	20	15	60
L56N 51+75W	.5	5	ND	7	23	13	1.97	1	12	12	88
L56N 52+00W	.4	9	5	6	30	17	2.36	ND	18	12	52
L56N 52+25W	.5	7	5	5	24	8	1.66	ND	10	11	53
L56N 52+50W	.5	8	ND	6	30	16	2.13	ND	24	12	51
L56N 52+75W	.3	ND	ND	10	34	29	2.39	ND	23	15	78
L56N 53+00W	.2	7	5	17	41	42	3.52	1	29	19	111
L56N 53+25W	.7	3	ND	4	25	9	1.67	ND	7	12	43
L56N 53+50W	.4	5	ND	6	33	14	2.17	1	17	12	84
L56N 53+75W	.5	4	ND	4	34	9	1.44	ND	9	9	41
L56N 54+00W	.3	6	15	9	34	24	2.76	ND	25	13	69
L56N 54+25W	.5	5	10	7	28	16	2.27	ND	17	14	46
L56N 54+50W	.4	6	5	5	23	8	1.84	ND	11	11	55
L56N 54+75W	.3	4	5	8	32	21	2.43	2	20	15	70
L56N 55+00W	.2	ND	5	9	21	39	2.61	1	17	16	79
L58N 50+50W	.4	4	15	10	46	22	2.57	ND	19	13	86
L58N 50+75W	.5	4	5	10	44	22	2.42	ND	17	14	80
L58N 51+00W	.3	4	5	10	16	53	2.26	ND	24	20	124
L58N 51+25W	.4	ND	5	12	20	57	2.84	ND	21	22	91
L58N 51+50W	.2	ND	5	21	36	77	3.48	1	39	25	80
L58N 52+75W	.4	11	15	10	36	52	3.07	1	29	16	49
L58N 53+00W	.2	6	10	11	38	53	3.19	1	27	13	49
L58N 53+25W	.6	6	5	6	24	11	1.88	ND	9	14	47
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CD PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L64N 54+75W	.1	ND	5	6	9	48	1.63	1	10	42	110
L64N 55+50W	.1	ND	ND	10	25	38	2.67	1	18	18	127
L64N 55+75W	.2	ND	ND	6	30	16	2.55	1	12	11	75
L64N 56+00W	.3	ND	ND	7	24	26	2.15	1	18	11	51
L64N 56+25W	.5	ND	ND	8	29	19	2.53	1	14	14	94
L64N 56+50W	.4	3	30	10	25	46	2.70	1	27	16	48
L64N 56+75W	.3	4	ND	12	40	40	3.41	1	23	21	53
L64N 57+00W	.3	6	ND	11	52	26	3.71	3	23	21	70
L64N 57+25W	.1	9	ND	13	44	30	3.15	2	26	19	73
L64N 57+50W	.3	8	ND	12	67	27	3.73	2	39	22	97
L64N 57+75W	.1	6	ND	14	41	34	3.58	2	24	28	205
L64N 58+00W	.1	7	ND	12	31	66	3.34	1	29	24	76
L64N 58+50W	.2	6	ND	14	34	71	2.98	2	30	20	72
L64N 58+75W	.2	5	30	14	36	48	3.21	2	30	23	68
L64N 59+00W	.3	7	ND	12	33	28	2.67	2	23	21	45
L64N 59+25W	.3	6	ND	8	31	22	2.54	2	19	17	61
L64N 59+50W	.3	6	ND	8	39	15	2.49	2	20	16	63
L64N 59+75W	.2	3	10	11	44	26	3.22	2	26	21	85
L64N 60+00W	.1	7	5	11	21	54	2.69	2	18	44	160
L66N 50+25W	.3	6	ND	9	34	25	2.95	2	18	19	57
L66N 50+50W	.5	4	ND	8	29	21	2.48	2	26	20	59
L66N 50+75W	.5	4	ND	7	27	15	2.07	2	15	17	36
L66N 51+00W	.3	4	ND	6	21	11	2.08	1	10	16	44
L66N 51+25W	.3	5	ND	7	27	14	2.48	2	16	18	69
L66N 51+50W	.7	5	ND	9	30	21	2.64	2	17	19	66
L66N 51+75W	.5	6	10	7	29	14	1.77	1	11	14	40
L66N 52+00W	.5	12	10	17	46	82	3.85	2	46	24	67
L66N 52+25W	.3	9	ND	11	32	28	2.59	2	22	18	115
L66N 52+50W	.6	6	ND	10	32	23	2.63	2	22	22	100
L66N 53+00W	.1	10	10	6	8	36	1.57	2	6	52	116
L66N 53+25W	.1	14	5	8	12	40	1.99	2	17	43	143
L66N 53+50W	.2	7	ND	7	13	35	2.00	2	12	44	102
L66N 53+75W	.1	29	ND	4	5	160	.77	2	5	64	45
L66N 54+00W	.1	11	10	7	11	58	1.69	2	11	49	74
L66N 54+25W	.1	ND	5	11	20	49	2.81	2	25	43	114
L66N 54+50W	.2	ND	15	7	18	16	1.78	2	11	19	61
L66N 54+75W	.1	3	10	9	22	32	2.42	1	20	21	78
L66N 55+00W	.1	ND	10	8	23	23	2.40	2	19	21	70
L66N 55+25W	.3	6	ND	7	18	14	1.93	2	14	19	56
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L66N 55+50W	.1	10	5	7	14	18	1.81	1	12	24	99
L66N 55+75W	.1	5	5	8	24	26	2.38	1	25	11	74
L66N 56+00W	.1	6	5	6	17	18	1.77	1	13	9	77
L66N 56+25W	.1	12	10	9	33	37	2.79	1	24	13	50
L66N 56+75W	.1	8	10	11	28	41	2.54	ND	22	13	64
L66N 57+00W	.1	6	ND	6	17	16	1.88	1	11	11	85
L66N 57+25W	.1	6	5	8	25	27	2.56	1	19	15	53
L66N 57+50W	.1	4	ND	8	27	18	2.45	ND	17	12	82
L66N 57+75W	.1	9	ND	8	28	30	2.49	ND	20	12	57
L66N 58+00W	.1	6	15	8	25	38	2.46	1	21	16	49
L66N 58+25W	.1	7	10	6	21	33	2.27	1	19	13	47
L66N 58+50W	.1	7	ND	7	14	28	1.84	1	18	30	96
L66N 58+75W	.1	6	5	9	14	63	2.59	1	18	59	117
L66N 59+00W	.1	6	5	10	21	33	2.58	1	24	23	90
L66N 59+25W	.1	8	10	9	25	32	2.66	1	22	13	48
L66N 59+50W	.2	6	ND	7	16	16	1.91	ND	15	14	62
L66N 59+75W	.1	5	ND	9	36	24	3.55	1	21	16	69
L66N 60+00W	.1	4	ND	12	41	32	2.92	1	31	13	83
L68N 50+75W	.2	5	5	7	28	26	2.36	1	16	11	39
L68N 51+00W	.3	5	10	12	41	37	2.85	1	26	13	76
L68N 51+25W	.2	5	5	10	40	69	3.50	1	34	17	53
L68N 51+50W	.3	7	10	10	37	33	2.67	1	27	14	62
L68N 51+75W	.4	4	10	8	32	16	3.00	1	21	14	110
L68N 52+00W	.4	5	5	4	21	8	1.70	ND	6	8	42
L68N 52+25W	.1	4	10	9	36	70	2.49	1	41	11	60
L68N 52+50W	.7	3	ND	21	68	188	5.25	2	76	22	128
L68N 52+75W	.2	5	15	7	28	45	2.20	1	21	14	40
L68N 53+00W	.5	7	10	10	32	28	2.57	1	19	15	91
L68N 53+25W	.5	5	5	5	26	12	2.16	1	12	11	61
L68N 53+50W	.3	6	15	6	27	29	2.51	1	18	13	44
L68N 53+75W	.1	7	ND	10	34	26	2.68	1	26	12	55
L68N 54+00W	.3	4	ND	6	28	14	1.97	ND	15	9	59
L68N 54+25W	.3	ND	10	6	26	16	2.24	1	15	11	60
L68N 54+50W	.2	5	5	10	37	30	2.80	1	24	14	80
L68N 54+75W	.1	3	ND	8	23	17	2.16	1	14	16	91
L68N 55+00W	.1	5	10	10	34	25	2.57	ND	24	15	64
L68N 55+25W	.3	5	10	8	28	11	1.95	ND	16	9	64
L68N 55+50W	.1	5	5	10	32	25	2.52	1	25	10	39
L68N 55+75W	.2	5	5	8	27	29	2.10	1	14	10	57
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

VANGEOCHEM LAB LIMITED

Paul Sterling

1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604) 986-5211
 E: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604) 251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -- NOT ANALYZED, *AU= GEOCHEM

CLIENT: E & B EXPLORATIONS REPORT#: 860431PA DATE RECEIVED: 86/09/02
 ANALYST: L. SALEKEN & M. TINDALL JOB#: 860431 DATE COMPLETED: 86/09/16
 CONTACT: 5061-CB PD#5587 INVOICE#: 860431NA COPY SENT TO: VANCOUVER OFFICE

ANALYST *W. Jones*

PAGE 1 OF 24

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L83N 35+00W	.1	8	5	6	26	17	2.17	1	12	12	30
L83N 35+25W	.1	5	ND	7	31	18	2.66	1	17	10	49
L83N 35+50W	.3	ND	ND	7	31	17	2.67	1	15	11	53
L83N 35+75W	.1	ND	ND	10	44	50	3.15	1	33	20	72
L83N 36+00W	.3	3	ND	8	30	19	2.48	1	16	12	50
L83N 36+50W	.3	6	ND	7	28	22	2.35	ND	17	11	50
L83N 36+75W	.3	5	ND	12	43	23	2.88	1	23	13	158
L83N 37+00W	.2	ND	ND	6	25	16	2.14	1	13	11	53
L83N 37+25W	.1	4	ND	7	34	20	2.12	1	17	13	63
L83N 37+50W	.2	9	ND	11	34	28	2.69	1	19	15	43
L83N 37+75W	.4	6	ND	8	31	17	2.40	1	13	12	81
L83N 38+00W	.4	4	ND	7	29	13	1.63	1	13	11	56
L83N 38+25W	1.1	6	5	18	39	41	3.16	3	15	16	174
L83N 38+50W	1.1	ND	10	26	27	124	5.04	2	15	16	154
L83N 38+75W	.4	4	ND	10	25	32	2.76	1	14	10	78
L83N 39+00W	.8	3	5	12	21	40	2.84	1	10	13	94
L83N 39+25W	.3	3	5	10	27	26	2.67	1	18	13	80
L83N 39+50W	.4	4	ND	8	25	17	2.39	1	16	14	50
L83N 39+75W	.2	5	15	21	23	38	3.58	2	18	21	219
L83N 40+00W	.1	ND	5	9	24	21	2.68	2	14	15	98
L83N 40+25W	.1	ND	ND	9	27	35	3.68	2	24	18	93
L83N 40+50W	.2	4	20	4	19	57	1.77	2	11	10	35
L83N 40+75W	.6	5	ND	6	21	21	2.23	1	11	13	50
L83N 41+00W	1.6	ND	100	7	15	125	7.20	9	7	28	101
L83N 41+25W	.1	ND	ND	11	30	43	3.18	1	24	18	97
L83N 41+50W	1.1	16	165	9	19	137	4.58	5	13	46	108
L83N 41+75W	.2	3	ND	9	24	31	2.46	1	15	14	70
L83N 42+00W	.4	4	ND	8	19	29	2.15	1	10	13	65
L83N 42+25W	.1	4	10	5	14	11	1.47	1	7	10	42
L83N 42+50W	.4	4	30	6	17	15	1.73	1	6	12	37
L83N 42+75W	.2	5	5	7	20	24	2.00	1	11	12	70
L83N 43+00W	.2	6	10	8	23	33	2.41	1	16	12	50
L83N 43+25W	.2	ND	ND	6	16	19	1.74	1	9	22	46
L83N 43+50W	.1	3	ND	7	14	14	1.85	1	6	10	50
L83N 43+75W	.1	ND	ND	7	17	86	2.25	1	9	15	187
L83N 44+00W	.4	8	15	12	12	23	2.57	1	8	14	95
L83N 44+25W	.1	4	ND	8	19	22	2.02	1	16	24	82
L83N 44+50W	.1	ND	ND	10	24	38	2.48	1	14	25	119
L83N 44+75W	.1	ND	ND	8	19	18	1.94	1	15	14	144
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

RECEIVED
 SEP 18 1986

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L83N 45+00W	.1	ND	ND	8	24	16	2.13	ND	20	17	123
L83N 45+25W	.1	ND	ND	6	22	14	2.10	ND	15	13	147
L83N 45+50W	.3	ND	ND	10	19	41	2.34	1	10	14	134
L83N 45+75W	.5	ND	ND	13	27	40	3.08	1	12	15	280
L83N 46+00W	.2	ND	10	7	21	30	1.92	ND	7	10	116
L83N 46+25W	.4	ND	10	8	20	30	2.35	1	12	14	131
L83N 46+50W	.2	ND	20	6	18	18	1.89	ND	10	11	79
L83N 46+75W	.4	ND	20	10	20	51	3.15	1	8	14	83
L83N 47+00W	.3	ND	10	7	20	16	2.06	1	9	12	102
L83N 47+25W	.1	ND	5	12	32	20	2.32	1	18	14	124
L83N 47+50W	.1	ND	ND	15	39	40	3.27	1	34	20	161
L83N 47+75W	.2	ND	ND	14	30	35	2.73	1	23	17	118
L83N 48+00W	.2	4	5	13	21	41	2.79	1	17	17	83
L83N 48+25W	.2	ND	10	13	31	29	2.83	1	23	18	144
L83N 48+50W	.2	3	ND	12	34	19	2.44	1	25	15	231
L83N 48+75W	.2	ND	10	11	27	28	2.38	1	17	14	225
L83N 49+00W	.3	4	10	10	17	35	2.51	1	11	15	171
L83N 49+25W	.5	6	15	14	19	53	3.11	1	14	18	203
L83N 49+50W	.3	ND	10	11	28	40	3.00	1	18	15	222
L83N 49+75W	.2	3	5	10	20	27	2.42	1	9	13	166
L83N 50+00W	.2	ND	ND	8	20	17	2.16	ND	17	12	140
L85N 35+00W	.1	6	ND	9	33	29	2.69	ND	21	14	51
L85N 35+25W	.1	ND	ND	7	28	13	2.43	ND	12	12	56
L85N 35+50W	.2	ND	ND	7	28	13	2.51	ND	12	13	58
L85N 35+75W	.1	3	ND	9	33	24	3.11	1	20	15	75
L85N 36+00W	.1	ND	ND	9	32	19	2.76	ND	21	14	64
L85N 36+25W	.2	ND	ND	5	26	16	2.18	ND	10	11	45
L85N 36+50W	.3	3	ND	7	31	29	3.14	2	11	16	85
L85N 36+75W	.3	5	ND	15	18	230	3.12	8	9	15	74
L85N 37+00W	.7	7	30	57	23	486	4.16	10	16	18	79
L85N 37+25W	.5	4	ND	17	27	290	3.94	9	13	16	81
L85N 37+50W	.2	5	5	9	27	221	2.56	1	12	10	58
L85N 37+75W	.4	5	ND	9	28	109	2.73	1	13	12	78
L85N 38+00W	.4	6	ND	7	26	20	1.99	1	11	13	55
L85N 38+25W	.3	5	ND	6	29	21	2.47	1	13	21	52
L85N 38+50W	.5	4	ND	5	25	16	2.27	1	7	12	42
L85N 38+75W	.3	5	ND	9	29	22	2.64	1	15	12	74
L85N 39+00W	.1	7	ND	11	33	44	2.95	1	26	14	77
L85N 39+25W	.2	6	ND	8	37	39	2.02	1	22	13	99
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L85N 39+50W	.1	4	ND	7	29	107	1.83	1	14	7	85
L85N 39+75W	.1	ND	ND	7	27	21	2.43	1	15	9	67
L85N 40+00W	.4	ND	ND	8	28	211	2.83	2	17	12	91
L85N 40+25W	.1	9	20	7	30	241	4.25	6	19	20	90
L85N 40+50W	.1	ND	5	8	31	49	2.62	2	20	16	83
L85N 40+75W	.1	ND	ND	10	44	51	2.99	2	35	14	129
L85N 41+00W	.3	3	120	7	20	94	3.32	6	11	18	86
L85N 41+25W	.3	7	ND	5	22	27	2.49	2	9	14	53
L85N 41+50W	.2	6	ND	11	33	69	3.67	5	28	22	96
L85N 41+75W	.1	ND	ND	11	31	38	3.02	1	23	17	82
L85N 42+00W	.1	ND	ND	9	26	61	3.40	1	16	15	88
L85N 42+25W	.5	ND	40	9	21	83	2.59	7	12	14	75
L85N 42+50W	.2	ND	ND	9	29	84	3.20	1	21	15	87
L85N 42+75W	.1	ND	ND	7	26	68	2.91	1	16	13	71
L85N 43+00W	.1	4	ND	11	32	129	3.83	2	24	21	101
L85N 43+25W	.4	ND	5	6	19	31	2.62	5	6	12	51
L85N 43+50W	.1	ND	10	7	23	18	2.41	1	11	11	59
L85N 43+75W	.1	5	ND	7	26	21	2.83	1	14	12	55
L85N 44+00W	.8	4	40	5	21	120	3.00	16	11	12	44
L85N 44+25W	.1	4	20	12	32	49	3.11	1	30	14	62
L85N 44+50W	.5	3	5	10	20	56	3.34	1	10	9	80
L85N 44+75W	.5	4	5	12	23	57	3.09	2	12	13	104
L85N 45+00W	.6	6	5	5	12	31	2.04	2	4	13	60
L85N 45+25W	.5	5	10	9	24	56	4.58	4	16	20	132
L85N 45+50W	.1	ND	10	11	32	178	4.05	2	27	19	99
L85N 45+75W	.1	3	ND	8	24	26	2.84	ND	14	17	83
L85N 46+00W	.1	ND	ND	13	28	40	3.16	1	21	16	121
L85N 46+25W	1.1	3	25	10	35	85	4.87	9	14	17	112
L85N 46+50W	.1	6	10	13	33	44	3.41	1	25	17	111
L85N 46+75W	1.1	4	20	9	28	58	3.85	2	12	26	165
L85N 47+00W	.5	7	5	5	20	16	2.15	1	8	10	64
L85N 47+25W	.4	8	30	11	30	41	4.58	2	15	17	208
L85N 47+50W	.1	6	ND	10	28	24	2.77	ND	20	14	119
L85N 47+75W	.1	4	ND	9	27	14	2.50	1	17	10	113
L85N 48+00W	.1	3	ND	13	26	19	2.87	1	13	13	139
L85N 48+25W	.1	3	ND	13	32	41	3.44	1	28	18	145
L85N 48+50W	.3	6	ND	12	28	39	3.41	1	22	19	161
L85N 48+75W	.2	3	10	19	30	99	4.20	2	24	24	203
L85N 49+00W	.6	6	10	22	42	146	4.51	1	39	22	320
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L85N 49+25W	.8	7	15	15	26	231	3.16	2	25	16	282
L85N 49+50W	.2	11	50	17	38	201	3.04	3	20	14	327
L85N 49+75W	.1	11	10	14	40	119	2.91	1	29	15	222
L85N 50+00W	.1	8	10	14	48	59	3.67	1	41	19	304
L87N 35+00W	.1	ND	5	14	44	78	3.74	ND	26	14	141
L87N 35+25W	.1	4	10	13	41	166	3.84	1	30	16	116
L87N 35+75W	.1	9	5	13	41	50	3.95	1	27	16	140
L87N 36+25W	.2	3	5	20	42	469	3.84	3	25	20	110
L87N 37+50W	.5	7	10	16	40	898	3.47	4	23	17	68
L87N 37+75W	1.1	5	5	23	39	1546	4.50	7	25	22	117
L87N 38+25W	.1	7	10	17	44	1007	3.87	3	28	19	74
L87N 38+50W	.1	9	ND	19	49	793	4.15	5	32	20	77
L87N 38+75W	.2	5	ND	6	26	32	2.22	ND	11	12	44
L87N 39+00W	.2	7	ND	10	34	31	2.86	ND	21	16	53
L87N 39+25W	.7	6	75	36	46	4941	4.26	5	32	31	81
L87N 39+50W	1.1	4	75	12	29	562	4.22	2	17	18	68
L87N 39+75W	1.1	3	60	17	29	1320	4.87	3	24	25	134
L87N 40+00W	1.1	ND	60	12	27	407	4.80	2	17	18	87
L87N 40+25W	1.8	ND	250	17	28	1245	9.16	4	24	22	115
L87N 40+50W	1.1	ND	50	18	44	436	5.24	2	46	20	150
L87N 40+75W	.5	4	40	8	29	231	2.91	3	22	14	64
L87N 41+00W	.6	14	15	12	45	217	4.05	4	27	19	91
L87N 41+25W	.7	23	165	9	14	151	3.69	8	11	26	81
L87N 41+50W	.3	9	5	14	41	241	3.34	3	28	19	73
L87N 41+75W	.6	8	5	13	45	72	4.27	3	31	22	153
L87N 42+00W	.6	6	15	13	37	110	3.74	3	26	19	125
L87N 42+25W	.2	8	5	10	36	37	3.45	1	22	19	117
L87N 42+50W	.1	3	15	15	46	140	3.42	2	36	17	74
L87N 42+75W	.1	4	5	14	43	74	2.77	1	38	15	69
L87N 43+00W	.2	5	15	10	38	86	3.06	2	25	19	79
L87N 43+50W	.1	11	5	8	30	80	3.22	2	15	16	57
L87N 43+75W	.2	5	20	18	34	844	4.50	5	29	24	102
L87N 44+00W	.7	8	45	34	20	714	6.20	2	16	22	126
L87N 44+25W	.2	10	10	13	33	160	3.84	2	24	20	95
L87N 44+50W	.1	3	15	11	32	153	3.84	2	21	15	113
L87N 44+75W	.6	6	5	9	31	49	3.97	1	15	17	111
L87N 45+00W	.3	6	20	10	30	60	3.90	1	17	18	121
L87N 45+25W	.2	5	30	11	26	123	3.77	3	13	14	117
L87N 45+50W	.5	6	15	9	25	65	3.00	2	15	16	85
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L87N 45+75W	.1	3	5	6	26	22	2.99	ND	10	11	106
L87N 46+00W	.3	5	10	7	29	45	3.27	ND	18	12	65
L87N 46+25W	.2	3	15	9	30	91	3.17	1	18	12	59
L87N 46+50W	.1	4	20	11	31	129	3.89	3	20	13	59
L87N 46+75W	.1	4	20	10	23	124	3.12	1	13	8	93
L87N 47+00W	.4	7	10	6	21	52	2.75	ND	11	10	103
L87N 47+25W	.5	5	15	7	21	74	2.93	1	10	10	110
L87N 47+50W	.5	6	5	8	25	41	3.14	ND	15	12	120
L87N 47+75W	.8	7	35	14	32	149	5.92	11	19	29	565
L87N 48+00W	.4	6	10	11	30	100	3.99	1	17	19	264
L87N 48+25W	.5	6	15	12	31	130	4.32	2	18	21	294
L87N 48+50W	.5	7	10	10	14	70	4.88	3	8	20	165
L87N 48+75W	.1	ND	10	8	26	115	3.07	1	17	17	121
L87N 49+00W	.1	ND	5	16	32	147	4.34	1	30	21	338
L87N 49+25W	.1	7	15	16	38	148	3.52	1	38	16	260
L87N 49+50W	.1	3	10	12	30	82	3.74	ND	24	18	316
L87N 49+75W	.1	4	5	17	34	100	4.72	1	29	22	469
L87N 50+00W	.1	6	30	12	25	39	3.45	ND	19	18	465
L89N 35+00W	.1	ND	5	11	37	33	3.51	ND	26	14	112
L89N 35+25W	.1	ND	5	10	39	26	3.50	ND	26	11	70
L89N 35+50W	.2	ND	10	10	41	36	3.60	ND	27	13	87
L89N 35+75W	.1	5	10	11	38	26	3.23	ND	26	12	88
L89N 36+00W	.1	ND	5	9	42	25	3.38	ND	19	11	69
L89N 36+25W	.1	3	10	9	33	37	2.97	1	16	10	83
L89N 36+50W	.1	ND	15	11	36	369	3.21	1	21	12	85
L89N 36+75W	.3	8	5	10	36	332	3.23	2	19	12	62
L89N 37+00W	.2	6	20	23	43	831	4.44	7	29	18	88
L89N 37+25W	.7	5	40	25	45	1870	3.97	4	33	19	98
L89N 37+50W	.6	6	5	15	45	1034	3.76	1	29	17	93
L89N 37+75W	.3	6	5	12	33	88	3.42	1	23	12	76
L89N 38+00W	.3	4	5	6	28	115	2.50	1	10	10	52
L89N 38+25W	.5	9	55	15	37	872	3.60	6	26	16	75
L89N 38+50W	.2	5	30	13	39	225	3.47	1	33	15	75
L89N 38+75W	.1	6	20	11	42	109	3.93	1	30	16	121
L89N 39+00W	.2	3	10	7	34	268	3.16	6	16	13	69
L89N 39+25W	.3	3	30	7	28	120	3.00	2	13	11	68
L89N 39+50W	.4	4	20	11	35	256	3.70	1	23	14	182
L89N 39+75W	.1	7	20	14	45	344	4.13	ND	42	19	97
L89N 40+00W	.3	6	20	11	31	134	3.44	1	19	16	146
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L89N 40+25W	.3	ND	10	8	26	71	2.88	1	15	11	97
L89N 40+50W	.7	5	15	8	26	181	3.36	1	16	11	102
L89N 40+75W	.2	ND	5	5	20	16	2.17	1	7	7	63
L89N 41+00W	.4	7	5	7	27	34	2.65	1	17	11	78
L89N 41+25W	.1	8	5	7	26	37	2.75	1	16	13	67
L89N 41+50W	.2	4	10	6	22	48	2.34	1	8	9	63
L89N 41+75W	.1	3	25	7	22	56	2.72	2	12	11	100
L89N 42+25W	.1	3	10	13	31	841	2.62	3	19	12	48
L89N 42+50W	.2	7	5	12	27	728	2.36	2	17	12	41
L89N 42+75W	.3	5	5	6	22	223	2.39	2	11	7	53
L89N 43+00W	.1	3	5	7	23	152	2.33	1	14	6	66
L89N 43+25W	.1	7	65	19	34	1038	3.85	4	42	25	151
L89N 43+50W	.1	5	5	11	30	195	2.54	2	16	12	78
L89N 43+75W	.1	3	10	8	29	332	2.60	2	20	12	60
L89N 44+00W	.1	3	10	7	27	266	2.40	2	18	12	58
L89N 44+25W	.1	ND	5	12	35	408	2.82	3	25	14	73
L89N 44+50W	.1	ND	10	5	27	271	1.93	1	12	7	51
L89N 44+75W	.1	5	5	9	31	815	1.56	2	13	8	37
L89N 45+00W	.1	ND	10	5	29	63	2.53	1	17	14	57
L89N 45+25W	.1	3	5	7	33	51	2.78	1	24	12	86
L89N 45+50W	.1	3	20	9	29	73	2.75	1	26	11	68
L89N 45+75W	.1	4	5	7	28	111	2.48	1	14	9	57
L89N 46+25W	.1	ND	15	6	22	46	2.50	1	9	7	68
L89N 46+50W	.1	3	20	8	25	104	3.12	1	17	12	77
L89N 46+75W	.1	6	20	9	23	137	2.91	2	14	11	62
L89N 47+00W	.1	5	10	7	20	61	2.68	3	9	8	89
L89N 47+50W	.1	7	25	7	20	99	3.41	4	11	9	58
L89N 47+75W	.1	5	10	9	19	104	2.35	2	9	11	64
L89N 48+00W	.1	3	20	7	25	107	2.71	1	13	11	81
L89N 48+25W	.1	3	10	8	24	106	2.68	2	14	9	69
L89N 48+50W	.2	3	20	5	19	55	2.45	2	9	9	72
L89N 48+75W	.3	8	30	17	23	441	3.65	4	17	12	80
L89N 49+50W	.1	5	10	8	22	265	2.45	2	11	9	97
L89N 49+75W	.3	7	5	6	20	132	2.75	3	8	13	99
L89N 50+00W	.2	ND	5	6	22	500	2.84	4	9	15	71
L91N 40+00W	.7	ND	10	8	29	55	2.51	ND	17	9	61
L91N 40+25W	.1	ND	25	8	28	163	2.76	1	20	8	82
L91N 40+50W	.1	5	20	9	28	135	2.91	1	22	11	78
L91N 40+75W	.2	6	15	11	24	195	2.98	2	16	16	81
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU #PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L91N 41+00W	.1	3	20	10	32	96	2.94	1	25	13	73
L91N 41+25W	.1	4	5	8	30	78	2.78	1	22	12	71
L91N 41+50W	.1	ND	10	10	29	124	2.86	2	19	13	69
L91N 41+75W	.1	5	5	11	25	429	2.46	5	15	11	58
L91N 42+00W	.1	4	5	13	30	413	3.09	4	20	16	75
L91N 42+25W	.1	ND	5	11	32	71	2.73	1	19	12	44
L91N 42+50W	.1	ND	5	11	34	61	3.02	1	22	13	48
L91N 42+75W	.1	ND	10	11	30	343	2.91	2	22	15	55
L91N 43+00W	.1	ND	15	6	23	53	2.72	1	10	14	45
L91N 43+25W	.3	ND	65	8	27	171	3.45	2	12	16	73
L91N 43+50W	.1	ND	10	10	27	201	2.73	5	19	14	57
L91N 43+75W	.1	ND	30	10	25	85	2.76	1	17	13	68
L91N 44+00W	.1	4	5	11	40	119	2.83	2	20	13	44
L91N 44+25E	.1	3	5	9	31	185	3.18	1	22	16	60
L91N 44+50W	.2	4	5	8	29	159	2.98	2	21	15	56
L91N 44+75W	.2	4	15	7	26	52	2.68	1	16	12	43
L91N 45+00W	.1	6	10	12	34	61	2.96	1	23	14	46
L91N 45+25W	.1	ND	5	11	31	51	2.76	1	22	16	44
L91N 45+50W	.2	ND	5	10	36	21	2.81	1	28	16	123
L91N 45+75W	.4	4	5	10	32	122	2.14	2	21	12	43
L91N 46+00W	.3	ND	5	11	33	162	2.20	2	27	13	46
L91N 46+25W	.3	ND	5	12	44	58	2.99	3	32	14	155
L91N 46+50W	.3	ND	5	14	43	70	3.09	3	34	15	171
L91N 46+75W	.1	4	10	11	39	61	2.59	2	32	15	92
L91N 47+00W	.1	3	5	11	40	57	2.69	3	33	15	99
L91N 47+25W	.1	ND	15	14	36	198	2.66	4	26	17	104
L91N 47+50W	.2	4	5	12	36	115	2.59	3	25	14	85
L91N 47+75W	.1	7	5	8	29	161	1.81	3	17	13	49
L91N 48+00W	.2	6	5	8	28	155	1.81	3	18	13	47
L91N 48+25W	.2	6	5	11	21	96	2.58	3	10	11	72
L91N 48+50W	.2	3	5	11	24	200	2.35	4	16	15	55
L91N 49+25W(A)	.1	ND	10	10	24	111	2.63	1	19	16	54
L91N 49+25W(B)	.2	4	5	9	23	192	2.05	3	14	14	53
L91N 49+50W	.3	3	10	10	28	224	2.49	4	19	18	62
L91N 49+75W	.2	8	10	10	25	89	2.94	3	15	15	54
L91N 50+00W	.2	9	15	10	26	93	3.00	3	15	15	55
L93N 40+00W	.1	ND	10	17	38	56	3.81	2	24	18	130
L93N 40+25W	.1	ND	10	8	28	38	2.97	1	10	12	61
L93N 40+50W	.3	ND	5	8	36	15	2.76	2	11	9	67
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L93N 40+75W	.1	ND	30	11	34	74	3.27	2	28	15	71
L93N 41+00W	.1	ND	10	10	33	34	3.77	1	23	22	102
L93N 41+25W	.4	ND	5	6	27	36	3.48	1	10	17	54
L93N 41+50W	.1	4	15	11	42	242	4.26	2	31	26	92
L93N 41+75W	.3	ND	10	7	26	25	2.96	1	13	14	70
L93N 42+00W	.2	6	10	16	35	113	3.60	1	24	17	65
L93N 42+25W	.2	4	10	14	38	110	3.43	1	23	16	73
L93N 42+50W	.2	4	20	11	38	53	3.26	ND	26	18	57
L93N 42+75W	.1	3	5	9	31	39	2.70	ND	17	13	66
L93N 43+00W	.1	7	40	12	32	85	2.95	ND	22	17	52
L93N 43+25W	.1	5	20	11	38	104	3.44	1	25	16	55
L93N 43+50W	.4	3	20	17	40	1076	3.59	8	26	20	60
L93N 43+75W	.4	ND	30	17	36	508	3.41	7	25	17	72
L93N 44+00W	.3	7	40	13	36	189	3.31	4	22	19	73
L93N 44+25W	.2	39	65	18	33	791	5.27	68	24	22	70
L93N 44+50W	.2	5	100	20	39	571	4.57	14	24	20	93
L93N 45+25W	.1	5	15	20	49	361	4.65	11	36	21	68
L93N 45+50W	.2	8	10	12	36	166	3.15	3	25	16	56
L93N 45+75W	.1	ND	30	10	28	67	2.76	1	16	14	76
L93N 46+00W	.3	4	10	5	18	8	1.67	ND	6	12	43
L93N 46+25W	.2	3	5	9	31	28	2.95	2	27	14	95
L93N 46+50W	.2	ND	5	5	22	10	2.07	1	12	12	60
L93N 46+75W	.3	3	5	5	25	14	2.33	1	10	15	49
L93N 47+00W	.2	ND	10	9	33	47	3.46	1	20	15	68
L93N 47+25W	.2	ND	5	8	26	76	2.26	1	15	13	52
L93N 47+50W	.1	ND	5	8	26	38	2.44	1	15	12	64
L93N 47+75W	.1	ND	5	6	23	16	2.06	ND	10	10	65
L93N 48+00W	.1	3	5	7	27	22	2.46	1	14	13	66
L93N 48+25W	.4	ND	5	7	28	31	2.82	1	16	16	71
L93N 48+50W	.1	5	5	7	33	51	2.77	2	17	13	70
L93N 48+75W	.1	ND	10	15	39	457	3.20	3	26	19	107
L93N 49+00W	.2	8	20	14	40	108	3.92	2	29	18	63
L93N 49+25W	.3	4	10	26	73	3045	5.77	18	55	30	179
L93N 49+75W	.2	5	10	15	37	879	2.69	4	22	15	145
L93N 50+00W	.2	6	5	6	33	95	2.67	4	14	16	117
L94N 57+25W	.2	3	20	11	26	110	3.88	3	15	16	111
L94N 57+50W	.2	ND	10	12	26	84	3.81	1	13	24	108
L94N 57+75W	.1	ND	10	13	17	49	3.85	3	10	21	112
L94N 58+00W	.1	7	10	14	25	160	4.14	1	19	19	179
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L94N 58+25W	.1	8	15	11	21	73	3.40	1	11	13	134
L94N 58+50W	.1	9	25	9	22	51	3.20	1	9	14	109
L94N 58+75W	.1	6	5	16	31	110	4.37	2	22	26	183
L94N 59+00W	.1	6	10	11	25	63	3.84	2	13	23	144
L94N 59+25W	.1	7	25	17	30	184	4.61	1	21	21	177
L94N 59+50W	.1	7	10	16	39	156	5.07	1	28	23	192
L94N 59+75W	.1	6	10	16	33	63	4.02	1	32	19	230
L94N 60+00W	.1	4	15	17	29	170	4.44	1	25	21	215
L94N 60+25W	.1	7	10	20	34	211	4.77	1	27	23	220
L94N 60+50W	.4	8	5	19	17	79	3.45	1	9	30	298
L94N 60+75W	.2	4	40	16	28	252	5.83	1	13	24	213
L94N 61+00W	.1	8	10	15	29	134	4.16	1	17	14	87
L94N 61+25W	.2	3	10	14	17	78	3.48	1	8	17	187
L94N 61+50W	.4	4	5	15	22	102	4.21	1	12	16	107
L94N 61+75W	.6	4	10	14	21	73	3.75	1	12	15	211
L94N 62+00W	.5	7	25	15	20	103	4.30	1	12	16	226
L94N 62+25W	.4	8	5	17	22	99	4.23	1	11	18	178
L94N 62+50W	.5	5	15	15	23	89	4.44	1	12	19	262
L94N 62+75W	.2	6	10	14	19	145	4.01	1	10	14	86
L94N 63+00W	.1	6	20	12	20	70	3.70	1	9	14	164
L94N 63+25W	.4	12	20	14	22	57	3.53	1	21	15	133
L94N 63+50W	.2	6	10	15	23	68	3.52	1	14	13	206
L94N 63+75W	.2	ND	5	14	21	36	3.22	1	9	12	233
L94N 64+00W	.1	16	25	26	35	851	5.36	10	29	24	179
L94N 64+25W	.3	6	15	17	26	145	3.95	1	20	15	219
L94N 64+50W	.6	ND	5	23	36	384	4.90	7	35	20	288
L94N 64+75W	.4	5	10	10	22	53	3.16	2	10	12	59
L95N 45+00W	.2	6	5	10	40	150	4.84	2	20	22	122
L95N 45+25W	.1	6	15	19	43	422	6.01	4	35	26	200
L95N 45+75W	.1	ND	5	8	32	24	2.89	1	16	13	133
L95N 46+25W	.5	5	10	10	33	71	4.14	4	16	16	148
L95N 46+50W	.2	3	5	11	29	78	3.42	2	14	15	144
L95N 47+00W	.5	ND	50	35	25	2079	7.01	6	19	17	110
L95N 47+25W	.1	ND	5	8	33	87	3.28	3	18	13	76
L95N 47+50W	.1	3	15	10	33	59	3.50	1	17	14	111
L95N 47+75W	.1	3	10	6	23	23	2.31	ND	10	10	69
L95N 48+00W	.1	ND	5	12	34	124	3.67	1	23	17	104
L95N 48+25W	.1	3	20	12	36	205	3.67	1	24	20	65
L95N 48+50W	.1	ND	15	9	30	75	3.37	1	17	11	78
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L95N 48+75W	.1	3	ND	8	29	35	3.25	1	16	17	71
L95N 49+00W	.2	4	15	9	28	77	2.98	1	18	16	65
L95N 49+25W	.2	ND	10	10	35	127	3.92	1	19	17	84
L95N 49+50W	.4	5	10	9	26	43	2.96	1	13	13	85
L95N 49+75W	.5	3	5	7	25	46	2.81	1	13	12	51
L95N 50+00W	.4	ND	10	10	30	91	3.05	1	18	12	75
L96N 57+25W	.3	ND	30	21	25	390	4.60	5	19	23	120
L96N 57+50W	.3	ND	55	14	23	326	4.53	3	15	18	110
L96N 57+75W	.6	ND	30	13	27	229	4.10	2	18	17	93
L96N 58+00W	.5	ND	35	10	25	134	3.90	3	13	17	109
L96N 58+25W	.4	4	25	17	28	251	4.56	7	18	20	105
L96N 58+50W	.6	7	20	13	28	220	4.07	3	17	21	125
L96N 58+75W	.6	5	10	10	23	86	3.79	2	13	21	155
L96N 59+00W	.7	4	20	16	26	197	4.57	5	16	27	177
L96N 59+25W	.5	5	25	8	23	69	3.49	1	10	19	76
L96N 59+50W	.5	4	25	13	27	216	4.28	2	16	21	127
L96N 59+75W	.5	3	40	14	30	254	4.59	2	19	22	121
L96N 60+00W	.6	ND	20	13	28	143	4.00	2	20	22	193
L96N 60+25W	.8	ND	50	12	27	837	4.21	3	20	38	198
L96N 60+50W	.4	ND	30	13	27	261	3.99	1	22	25	228
L96N 60+75W	.6	ND	10	10	19	62	3.02	1	14	15	126
L96N 61+00W	.5	ND	30	14	21	254	4.09	1	15	18	89
L96N 61+25W	.7	5	20	10	19	119	3.25	1	10	29	252
L96N 61+50W	.6	6	35	13	20	149	3.93	1	12	29	269
L96N 61+75W	.4	10	95	16	23	535	4.98	3	14	24	101
L96N 62+00W	.5	7	20	13	24	163	4.07	2	13	19	123
L96N 62+25W	.3	6	25	14	22	155	3.82	2	12	22	194
L96N 62+50W	.4	10	10	12	28	176	3.66	1	17	16	75
L96N 62+75W	.5	7	35	14	23	116	3.96	1	14	16	276
L96N 63+00W	.5	7	10	15	24	111	3.85	2	13	20	209
L96N 63+25W	.5	ND	75	11	18	375	4.92	2	11	18	78
L96N 63+50W	.4	ND	20	11	18	75	3.35	1	9	15	200
L96N 63+75W	.2	ND	5	12	19	63	3.74	1	9	20	276
L96N 64+00W	.3	8	15	12	20	57	3.07	1	11	15	160
L96N 64+25W	.3	7	10	12	21	131	2.93	2	13	16	140
L96N 64+50W	.3	4	30	18	28	487	4.18	4	17	19	119
L96N 64+75W	.4	9	30	15	22	133	3.50	3	13	18	108
L96N 65+00W	.3	5	10	14	21	141	3.28	2	15	14	131
L96N 65+25W	.4	ND	5	16	31	447	4.12	6	28	20	159
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L96N 66+50W	.5	4	5	9	17	136	3.02	1	12	15	78
L96N 65+75W	.6	7	15	15	25	347	3.30	2	20	13	119
L96N 66+00W	.3	4	15	14	31	218	3.55	1	19	10	123
L96N 66+25W	.1	9	30	13	24	541	3.35	2	17	12	86
L96N 66+50W	.5	9	20	9	18	309	2.43	1	11	14	70
L97N 45+00W	.3	10	20	11	24	89	3.78	3	14	22	288
L97N 45+25W	.1	5	5	14	40	64	3.50	ND	28	13	86
L97N 45+50W	.2	3	5	12	35	111	3.26	4	29	14	133
L97N 45+75W	.7	5	5	10	29	31	2.90	ND	19	12	163
L97N 46+00W	.1	9	5	7	26	21	2.46	ND	14	12	103
L97N 46+25W	.1	ND	15	14	42	69	4.19	ND	32	26	100
L97N 46+50W	.2	3	5	7	25	24	2.57	ND	14	12	109
L97N 46+75W	.1	4	5	10	27	54	2.74	2	18	10	86
L97N 47+00W	.1	3	25	12	34	56	3.18	ND	25	13	50
L97N 47+25W	.1	4	10	11	33	53	3.11	ND	24	15	51
L97N 47+50W	.1	4	10	12	37	62	3.37	ND	25	15	56
L97N 47+75W	.1	ND	5	11	35	58	3.49	ND	24	15	157
L97N 48+00W	.1	14	95	32	13	1020	6.28	3	15	18	107
L97N 48+25W	.1	20	90	40	10	1393	6.92	3	13	19	125
L97N 48+50W	.1	5	15	12	28	157	3.42	1	27	17	56
L97N 48+75W	.2	7	15	12	31	143	3.41	1	24	17	55
L97N 49+00W	.1	4	5	15	39	136	3.82	1	34	18	60
L97N 49+50W	.1	3	5	29	147	349	4.60	1	204	15	63
L97N 49+75W	.2	3	5	7	24	27	2.85	1	14	14	61
L97N 50+00W	.2	ND	20	7	25	31	2.99	1	15	14	69
L104N 50+25W	.2	ND	5	14	40	195	3.81	ND	35	24	116
L104N 50+50W	.1	ND	5	18	37	128	3.96	3	33	25	216
L104N 50+75W	.1	ND	5	12	41	91	3.86	1	33	21	171
L104N 51+25W	.4	3	5	13	30	229	3.64	2	26	27	175
L104N 51+50W	.2	3	5	13	31	257	3.82	2	28	28	182
L104N 51+75W	.4	ND	5	18	24	466	3.26	3	18	34	210
L104N 52+00W	.2	ND	ND	12	26	179	4.34	3	14	18	155
L104N 52+25W	.1	ND	ND	11	31	279	3.78	2	23	19	126
L104N 52+50W	.1	ND	25	9	28	279	4.01	2	17	20	129
L104N 52+75W	.5	ND	15	9	24	276	3.79	1	14	20	158
L104N 53+00W	.1	5	20	6	23	166	3.20	ND	10	16	78
L104N 53+25W	.1	ND	20	9	32	122	3.67	ND	22	16	113
L104N 53+50W	.9	16	65	12	26	869	4.71	4	21	28	163
L104N 53+75W	.4	11	30	18	41	445	3.73	3	97	19	133
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L104N 54+00W	.5	8	ND	13	25	138	3.73	3	32	17	139
L104N 54+25W	.2	5	10	5	24	40	2.98	4	9	13	72
L104N 54+50W	.1	ND	ND	8	26	104	3.16	2	15	11	85
L104N 54+75W	.1	8	70	14	26	1509	4.46	4	17	14	99
L104N 55+00W	.1	6	50	12	23	1424	3.94	1	14	12	78
L104N 55+25W	.1	3	15	14	36	449	4.59	1	32	15	110
L104N 55+50W	.2	5	10	9	35	60	2.51	1	47	9	34
L104N 55+75W	.1	5	20	17	52	646	3.54	2	108	14	43
L104N 56+00W	.1	ND	30	21	57	650	3.74	2	149	12	57
L104N 56+25W	.3	4	330	17	30	955	5.02	2	34	20	84
L104N 56+50W	.1	ND	25	10	30	486	3.61	2	24	16	82
L104N 56+75W	.1	3	40	13	34	496	4.02	2	25	18	64
L104N 57+00W	.2	3	10	20	25	719	2.81	2	18	17	51
L104N 57+25W	.1	5	20	9	27	327	3.50	1	22	15	64
L104N 57+50W	.1	ND	20	11	29	85	3.91	1	17	17	77
L104N 57+75W	.1	ND	10	13	39	186	4.21	1	35	20	88
L104N 58+00W	.1	ND	15	12	34	156	4.14	1	27	19	81
L104N 58+25W	.1	ND	5	15	24	154	3.48	1	19	16	89
L104N 58+50W	.1	ND	10	11	29	138	2.92	1	21	13	59
L104N 59+00W	.5	ND	5	26	74	43	3.98	ND	158	12	92
L104N 59+25W	.1	3	30	12	29	175	3.38	1	30	14	56
L104N 59+50W	.1	ND	25	10	26	152	3.45	1	22	14	60
L104N 59+75W	.1	ND	30	10	25	153	3.56	1	16	13	85
L104N 60+00W	.2	ND	40	9	25	272	2.87	1	19	11	73
L104N 60+75W	.1	ND	20	15	43	268	4.55	1	25	15	120
L104N 61+00W	.1	ND	20	11	25	182	3.39	1	19	12	64
L104N 61+25W	.3	ND	15	8	23	63	3.16	1	10	10	64
L104N 61+50W	.1	ND	35	11	27	373	3.79	1	21	16	80
L104N 61+75W	.1	ND	40	13	20	270	4.31	1	20	18	143
L104N 62+00W	.2	ND	65	12	17	313	3.40	1	14	13	114
L104N 62+25W	.3	ND	35	8	19	132	3.80	1	12	18	79
L104N 62+50W	.4	ND	35	8	17	151	3.05	1	8	14	48
L104N 62+75W	.1	ND	20	19	22	719	3.57	1	15	15	64
L104N 63+00W	.1	ND	25	11	20	391	3.76	1	16	12	72
L104N 63+25W	.3	4	45	12	21	761	3.82	1	14	11	57
L104N 63+50W	.4	3	35	10	18	340	4.33	1	10	14	85
L104N 63+75W	.3	ND	30	10	19	338	4.66	1	10	13	89
L104N 64+00W	.3	ND	30	17	19	867	4.54	1	19	14	111
L104N 64+25W	.2	3	55	13	19	614	4.40	1	11	15	97
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L104N 64+50W	.1	6	60	16	22	1430	3.79	2	13	15	71
L104N 64+75W	.2	4	ND	14	21	410	4.03	1	11	14	106
L104N 65+00W	.2	3	45	9	18	114	3.70	1	8	10	83
L104N 65+25W	.1	4	30	9	19	125	3.22	1	9	12	85
L104N 65+50W	.4	5	40	12	22	473	4.19	1	15	16	118
L104N 65+75W	.2	3	40	8	19	217	3.14	1	11	11	89
L104N 66+00W	.1	ND	60	14	22	793	3.98	1	14	14	85
L104N 66+25W	.1	ND	25	14	26	517	4.17	2	21	25	188
L104N 66+50W	.1	6	35	13	14	425	4.90	1	10	25	142
L104N 66+75W	.2	ND	95	7	17	367	3.95	2	11	25	88
L104N 67+00W	.2	4	80	12	29	526	4.95	4	19	25	124
L104N 67+25W	.1	ND	15	11	19	460	3.11	1	16	22	141
L104N 67+50W	.2	ND	35	13	23	189	3.91	2	12	20	135
L104N 67+75W	.2	5	20	11	17	236	2.94	2	7	14	91
L104N 68+00W	.2	12	20	10	21	228	3.04	2	10	14	62
L104N 68+25W	.2	5	25	10	21	100	3.34	2	13	16	126
L104N 68+50W	.4	5	10	7	17	78	2.43	2	7	18	75
L104N 68+75W	.1	5	30	15	28	215	4.28	1	24	24	126
L104N 69+25W	.4	3	10	12	19	53	3.27	1	8	15	194
L104N 69+50W	.2	5	20	11	15	86	3.50	1	7	17	141
L104N 69+75W	.6	6	15	11	17	139	3.44	3	17	21	172
L104N 70+00W	.4	6	50	9	17	128	3.57	2	11	15	120
L106N 50+25W	.2	ND	15	12	38	53	3.60	1	36	22	197
L106N 50+50W	.2	ND	5	18	49	105	4.55	2	51	26	242
L106N 50+75W	.2	ND	5	12	44	44	4.51	3	35	23	144
L106N 51+00W	.6	ND	5	17	41	104	3.85	3	26	28	489
L106N 51+25W	.4	5	20	11	35	84	3.25	2	23	25	434
L106N 51+50W	.4	10	5	15	42	97	3.81	2	26	25	532
L106N 52+00W	.2	3	10	13	36	82	3.79	2	29	23	168
L106N 52+25W	.1	ND	10	13	38	83	3.87	2	31	25	163
L106N 52+50W	.1	ND	15	13	35	269	3.39	5	33	21	125
L106N 53+00W	.2	ND	5	11	42	49	3.81	1	30	19	143
L106N 53+25W	.1	3	5	13	43	53	3.84	2	33	18	146
L106N 53+50W	.2	ND	5	12	31	46	3.18	2	23	19	214
L106N 53+75W	.2	ND	5	11	34	53	3.37	2	24	17	230
L106N 54+25W	.6	ND	5	12	33	79	3.63	3	33	21	210
L106N 54+75W	.4	6	10	6	30	44	3.06	5	16	20	97
L106N 55+00W	1.3	61	110	50	16	2303	7.97	43	13	20	244
L106N 55+25W	.1	23	50	35	27	3771	5.37	24	22	20	89
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L106N 55+50W	.1	27	40	30	24	3370	4.83	21	19	14	71
L106N 55+75W	.1	ND	35	8	23	236	3.71	4	14	13	57
L106N 56+00W	.1	ND	30	10	29	177	3.53	2	21	12	70
L106N 56+25W	.1	ND	20	11	26	343	3.41	1	21	13	68
L106N 56+50W	.1	ND	40	11	26	323	3.31	2	21	13	66
L106N 56+75W	.1	7	30	11	28	221	4.36	2	24	15	86
L106N 57+25W	.1	ND	5	6	16	61	1.49	ND	13	12	44
L106N 57+50W	.1	ND	15	12	36	130	3.48	1	31	17	75
L106N 57+75W	.1	ND	15	10	27	80	3.21	1	20	14	77
L106N 58+00W	.1	ND	30	13	9	531	3.72	1	8	11	67
L106N 58+25W	.5	ND	5	22	27	126	4.38	1	58	18	114
L106N 58+50W	.1	ND	10	18	27	172	3.89	2	34	15	111
L106N 58+75W	.1	ND	15	18	26	175	3.87	1	33	14	111
L106N 59+00W	.2	ND	10	13	25	113	3.56	2	24	14	167
L106N 59+25W	.1	3	25	15	27	249	4.02	1	26	15	75
L106N 59+50W	.1	ND	35	17	31	380	4.33	1	29	14	70
L106N 60+00W	.1	ND	5	9	29	126	3.13	1	21	14	63
L106N 60+25W	.1	ND	5	10	31	69	3.00	1	21	13	80
L106N 60+50W	.1	ND	5	10	26	38	2.51	1	27	12	48
L106N 60+75W	.1	ND	25	8	15	46	3.43	1	11	13	57
L106N 61+00W	.3	7	10	11	18	182	3.89	1	20	12	85
L106N 61+25W	.3	5	10	11	18	159	3.61	1	17	12	97
L106N 61+50W	.4	ND	30	12	22	207	3.86	1	17	14	119
L106N 62+00W	.1	ND	20	8	22	319	3.03	2	16	11	45
L106N 62+25W	.1	ND	65	10	21	198	3.71	1	18	10	71
L106N 62+75W	.1	4	65	8	23	293	3.64	2	11	18	51
L106N 63+00W	.1	3	50	10	23	317	4.37	2	16	17	55
L106N 63+25W	.1	3	40	14	24	299	4.01	1	20	13	68
L106N 63+75W	.2	ND	20	13	18	178	4.05	1	13	15	88
L106N 64+50W	.3	ND	55	13	23	488	4.01	2	20	23	104
L106N 64+75W	.3	ND	90	8	10	132	3.40	1	7	11	83
L106N 65+00W	.1	5	75	15	17	566	4.78	1	13	15	80
L106N 65+25W	.2	ND	75	11	16	251	4.67	1	12	10	142
L106N 65+50W	.4	ND	40	10	16	240	4.54	1	10	12	87
L106N 65+75W	.2	ND	35	7	14	127	3.41	1	8	11	101
L106N 66+00W	.1	ND	100	15	10	665	4.40	1	8	17	124
L106N 66+25W	.1	ND	25	13	20	254	4.06	1	17	11	129
L106N 66+50W	.1	ND	25	11	21	365	4.90	1	15	20	181
L106N 66+75W	.1	ND	15	10	19	169	3.45	1	12	9	152
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L106N 67+00W	.1	ND	45	8	17	168	3.46	1	10	9	102
L106N 67+25W	.1	ND	410	10	19	244	4.21	1	13	13	138
L106N 67+50W	.1	ND	20	12	21	287	4.54	1	14	13	143
L106N 67+75W	.1	3	75	12	21	668	3.74	1	14	10	60
L106N 68+00W	.1	ND	65	13	23	786	3.98	1	15	10	61
L106N 68+25W	.1	ND	65	10	19	288	3.43	2	11	11	68
L106N 68+50W	.1	ND	85	12	21	234	3.35	1	11	9	55
L106N 68+75W	.1	ND	25	12	23	211	4.13	1	13	15	129
L106N 69+00W	.1	ND	25	10	19	91	3.32	1	8	10	96
L106N 69+25W	.1	ND	30	11	19	159	3.65	2	12	13	91
L106N 69+50W	.1	ND	30	13	22	131	3.87	2	13	14	123
L106N 69+75W	.1	3	85	13	21	221	3.93	1	13	15	130
L106N 70+00W	.1	ND	45	9	17	188	3.45	1	11	11	108
L108N 40+25W	.1	3	5	15	49	318	3.69	3	34	16	77
L108N 40+50W	.1	ND	5	15	49	195	3.77	2	32	13	85
L108N 40+75W	.1	ND	5	14	48	84	3.48	1	26	12	74
L108N 41+00W	.1	ND	5	13	43	139	3.60	2	31	14	100
L108N 41+25W	1.1	ND	5	23	74	582	5.57	3	69	25	150
L108N 41+50W	.1	ND	5	22	70	365	5.08	5	67	23	143
L108N 41+75W	.3	ND	15	12	34	63	2.91	2	25	13	67
L108N 42+00W	.1	3	10	13	43	200	3.23	3	52	25	88
L108N 42+25W	.1	6	10	14	36	267	2.92	3	36	26	83
L108N 42+50W	.1	16	10	10	21	159	1.69	3	23	29	50
L108N 42+75W	.1	ND	15	13	46	122	3.44	4	32	13	77
L108N 43+00W	.1	ND	10	16	48	259	3.75	5	39	14	144
L108N 43+25W	.1	ND	5	16	58	214	4.21	8	45	15	124
L108N 43+50W	.1	ND	5	15	58	204	3.94	7	47	15	98
L108N 43+75W	.1	ND	15	17	53	108	3.85	6	38	13	72
L108N 44+00W	.1	ND	10	17	55	85	3.88	4	41	12	63
L108N 44+25W	.1	ND	5	18	56	95	4.16	2	44	12	65
L108N 44+50W	.6	4	5	13	42	361	3.42	3	41	13	90
L108N 44+75W	.1	6	10	19	39	223	3.94	1	38	18	92
L108N 45+00W	.1	ND	5	14	41	71	3.69	1	30	13	80
L108N 45+25W	.1	ND	5	11	35	66	3.20	1	28	13	132
L108N 45+50W	.1	ND	10	9	29	35	2.86	2	13	11	91
L108N 45+75W	.1	ND	5	13	39	126	3.68	1	25	15	95
L108N 46+00W	.1	ND	5	11	35	70	3.09	1	19	11	93
L108N 46+25W	.1	3	15	14	35	123	3.43	1	22	20	117
L108N 46+50W	.1	ND	10	9	31	44	3.00	1	19	9	69
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CD PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L108N 46+75W	.4	3	10	14	29	156	3.39	2	23	30	157
L108N 47+00W	ND	ND	5	8	28	29	2.36	ND	14	8	122
L108N 47+25W	ND	4	10	13	31	122	3.38	ND	23	14	142
L108N 47+50W	.2	ND	30	12	30	158	3.60	1	20	14	135
L108N 47+75W	ND	ND	10	11	39	38	3.33	1	23	11	70
L108N 48+00W	ND	ND	10	12	30	95	3.26	1	21	23	89
L108N 48+25W	ND	ND	10	12	38	59	3.53	ND	26	14	61
L108N 48+50W	ND	ND	5	10	35	23	2.97	ND	18	10	77
L108N 48+75W	ND	ND	10	8	30	19	2.88	1	20	12	100
L108N 49+00W	.1	ND	5	12	30	35	3.42	ND	17	13	103
L108N 49+25W	ND	ND	5	12	39	29	3.80	1	30	14	76
L108N 49+50W	.1	ND	10	13	44	48	3.65	ND	29	14	60
L108N 49+75W	.2	ND	10	8	32	19	2.69	1	13	10	66
L108N 50+00W	.2	ND	10	11	33	25	3.14	2	16	10	80
L108N 50+25W	.3	ND	10	14	41	357	3.66	3	30	16	212
L108N 50+50W	.2	ND	5	12	39	97	3.44	2	27	15	149
L108N 50+75W	.4	ND	10	14	33	80	3.17	5	18	14	185
L108N 51+00W	ND	ND	5	11	37	39	3.37	1	23	12	146
L108N 51+25W	.5	ND	5	13	35	174	3.71	2	25	17	387
L108N 51+50W	1.0	7	25	19	51	5251	4.37	6	51	59	1498
L108N 51+75W	.5	ND	5	14	35	85	3.64	5	24	16	194
L108N 52+00W	.2	ND	5	11	34	33	3.29	1	20	11	152
L108N 52+25W	.2	ND	5	10	34	358	3.08	3	21	13	130
L108N 52+50W	.7	ND	10	13	42	1283	3.43	6	35	18	153
L108N 52+75W	.7	ND	5	7	22	26	2.18	2	7	11	82
L108N 53+00W	.1	ND	10	12	32	986	3.37	8	20	16	274
L108N 53+25W	.1	ND	15	10	32	46	3.34	4	22	13	128
L108N 53+50W	.1	ND	10	8	27	23	2.72	1	16	10	97
L108N 53+75W	.7	4	15	12	38	88	3.67	2	33	17	115
L108N 54+00W	.6	ND	5	13	39	90	3.78	1	36	19	124
L108N 54+25W	.2	ND	5	10	30	20	3.06	2	12	13	113
L108N 54+50W	ND	ND	15	13	40	169	4.01	3	38	19	229
L108N 54+75W	.3	ND	10	14	40	376	4.46	5	37	23	690
L108N 55+00W	.1	3	10	12	32	38	3.57	3	19	11	211
L108N 55+25W	ND	9	20	20	40	255	4.42	2	35	20	107
L108N 55+50W	.3	7	20	19	29	560	3.68	4	19	18	121
L108N 55+75W	.2	6	5	20	30	594	3.86	5	19	20	127
L108N 56+00W	.1	11	20	22	29	560	4.34	8	23	17	115
L108N 56+25W	.2	ND	10	12	33	159	3.26	5	18	11	123
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L108N 56+50W	.1	ND	5	16	37	234	3.93	5	23	13	136
L108N 56+75W	.1	ND	ND	13	31	88	3.97	4	19	13	138
L108N 57+00W	.3	8	5	7	25	57	3.27	6	10	17	93
L108N 57+25W	.1	10	20	18	26	269	4.07	4	18	16	106
L108N 57+50W	.1	ND	30	15	26	190	4.13	1	21	10	97
L108N 58+50W	.1	ND	10	17	22	198	4.76	ND	37	10	78
L108N 58+75W	.1	ND	20	14	25	177	4.19	ND	24	11	94
L108N 59+00W	.1	ND	15	15	29	125	4.15	ND	25	10	89
L108N 59+25W	.1	ND	15	14	31	124	4.03	1	25	12	87
L108N 59+50W	.1	ND	5	17	21	184	4.72	ND	19	7	82
L108N 59+75W	.2	ND	25	19	22	121	5.36	ND	21	8	101
L108N 60+00W	.2	ND	20	13	24	178	3.26	1	20	15	70
L108N 60+25W	.1	ND	10	12	24	61	3.71	ND	15	12	85
L108N 60+50W	.3	ND	10	17	14	136	4.55	ND	12	23	99
L108N 60+75W	.1	ND	10	9	18	71	3.25	ND	12	13	76
L108N 61+00W	.2	ND	15	13	21	160	4.17	ND	18	11	91
L108N 61+25W	.1	ND	10	14	18	149	4.33	ND	12	13	79
L108N 61+75W	.6	ND	15	23	33	632	4.69	ND	28	12	92
L108N 62+00W	.2	4	10	10	18	58	3.21	1	9	14	86
L108N 62+25W	.1	ND	25	15	21	323	3.42	1	14	12	72
L108N 62+50W	.1	ND	20	14	22	316	3.48	1	19	10	69
L108N 62+75W	.1	ND	175	15	21	189	4.30	1	15	11	115
L108N 63+00W	.1	ND	25	14	20	173	4.04	1	12	11	108
L108N 63+25W	.1	ND	20	12	17	109	3.71	2	8	11	86
L108N 63+50W	.1	ND	20	13	23	146	3.92	1	16	14	123
L108N 63+75W	.1	ND	35	10	20	173	3.81	ND	11	12	76
L108N 64+00W	.1	7	15	12	20	170	3.89	1	12	12	75
L108N 64+25W	.1	7	70	10	21	171	3.52	1	11	10	82
L108N 64+50W	.1	8	70	13	23	408	4.13	1	16	13	52
L108N 64+75W	.1	ND	50	12	23	420	3.77	ND	15	9	66
L108N 65+00W	.1	ND	50	14	23	509	4.85	ND	17	11	124
L108N 65+25W	.1	ND	40	13	24	463	5.00	ND	17	11	122
L108N 65+50W	.1	ND	40	13	19	350	4.15	ND	11	12	118
L108N 66+50W	.2	7	25	11	18	200	3.67	1	12	14	113
L108N 66+75W	.1	4	200	12	19	220	3.94	1	13	12	124
L108N 67+00W	.1	5	45	9	22	153	3.74	1	9	10	80
L108N 67+25W	.1	8	45	7	15	128	3.07	1	7	11	90
L108N 67+50W	.1	13	45	11	20	286	3.90	2	10	11	71
L108N 67+75W	.2	11	75	12	21	448	3.87	2	13	13	57
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L108N 68+00W	.1	3	50	10	15	192	3.09	ND	15	13	66
L108N 68+25W	.1	ND	100	11	19	130	3.00	1	12	13	118
L108N 68+50W	.1	ND	35	9	17	116	3.10	1	12	13	118
L108N 68+75W	.1	ND	15	11	22	118	3.72	ND	13	12	146
L108N 69+00W	.1	7	5	9	17	102	3.00	1	10	15	80
L108N 69+25W	.1	4	35	8	18	68	2.91	1	7	14	104
L108N 69+50W	.1	ND	25	14	22	323	3.99	1	15	15	97
L108N 69+75W	.1	4	25	11	19	169	3.46	1	9	14	57
L108N 70+00W	.1	6	35	10	24	155	3.35	2	11	17	64
L110N 42+00W	.1	4	5	11	40	44	2.66	1	22	15	53
L110N 42+25W	.1	ND	56	16	56	196	4.13	1	62	5	88
L110N 42+50W	.1	ND	5	14	44	72	3.22	1	25	13	90
L110N 42+75W	.1	ND	5	14	46	200	3.45	4	48	10	115
L110N 43+00W	.2	ND	10	14	54	396	3.79	2	59	11	116
L110N 43+25W	.2	ND	10	15	56	500	3.73	ND	56	11	107
L110N 43+50W	.4	ND	15	21	71	610	4.69	ND	74	14	195
L110N 43+75W	.1	5	5	10	39	49	2.70	1	22	16	67
L110N 44+00W	.1	ND	10	11	40	68	2.92	1	23	17	67
L110N 44+25W	.3	ND	5	15	57	350	4.00	ND	57	11	146
L110N 44+50W	.3	ND	15	14	51	356	3.59	1	44	14	118
L110N 44+75W	.1	ND	5	13	44	139	3.14	1	33	17	63
L110N 45+00W	.1	ND	15	14	46	218	3.44	1	32	17	87
L110N 45+25W	.8	ND	15	19	65	1081	4.70	ND	58	17	145
L110N 45+50W	.1	5	15	12	41	62	3.16	ND	23	18	118
L110N 45+75W	.2	ND	10	21	37	346	4.59	3	29	21	92
L110N 46+00W	.1	3	10	18	48	273	4.10	ND	34	19	81
L110N 46+50W	.1	ND	25	23	11	617	4.10	1	11	13	110
L110N 46+75W	.1	21	50	27	17	1453	5.16	1	15	26	115
L110N 47+00W	.1	ND	15	19	27	480	3.97	ND	20	20	89
L110N 47+25W	.1	13	60	28	18	1253	5.70	2	15	26	128
L110N 47+50W	.1	6	5	15	30	208	3.56	ND	21	20	65
L110N 47+75W	.1	8	10	10	29	55	3.01	ND	16	21	88
L110N 48+00W	.1	ND	15	15	35	100	3.69	ND	24	18	67
L110N 48+25W	.1	ND	5	13	34	68	3.49	ND	20	24	86
L110N 48+50W	.1	ND	15	11	36	53	3.17	1	23	18	63
L110N 48+75W	.1	ND	20	13	24	198	3.95	ND	15	22	78
L110N 49+00W	.1	ND	5	10	34	26	2.91	1	22	18	82
L110N 49+25W	.1	6	5	11	30	38	2.63	1	20	18	58
L110N 49+50W	.4	ND	5	12	35	337	3.18	3	28	19	69
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CD PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L110N 49+75W	.1	6	5	10	31	63	2.83	1	21	9	51
L110N 50+00W	.1	4	5	9	31	49	2.88	3	19	11	64
L110N 50+25W	.1	5	10	19	37	212	4.12	2	31	21	86
L110N 51+00W	.3	7	20	8	22	56	2.49	1	14	13	78
L110N 51+25W	2.1	5	15	10	25	73	2.97	1	14	12	82
L110N 51+50W	.1	ND	20	12	30	67	3.52	ND	24	14	84
L110N 51+75W	.3	4	25	11	28	91	3.25	1	16	17	71
L110N 52+00W	.4	5	5	7	26	34	2.54	1	16	11	78
L110N 52+25W	.2	4	5	10	31	97	3.12	1	21	10	58
L110N 52+50W	.1	ND	5	12	41	75	3.46	ND	29	9	65
L110N 52+75W	.1	4	10	12	39	71	3.36	ND	30	11	69
L110N 53+00W	.1	ND	25	11	34	90	3.51	ND	30	11	99
L110N 53+25W	.1	ND	5	11	33	85	3.36	1	29	13	92
L110N 53+50W	.1	ND	5	14	36	62	3.77	ND	37	7	111
L110N 53+75W	.1	ND	5	10	30	35	3.00	1	18	12	91
L110N 54+00W	.3	7	5	10	30	80	2.73	2	24	15	60
L110N 54+25W	.3	11	5	8	28	71	2.45	2	20	14	52
L110N 54+50W	.3	10	20	10	31	85	2.86	2	25	14	61
L110N 54+75W	.1	ND	15	10	33	41	2.80	4	20	8	143
L110N 55+00W	.1	ND	10	11	37	46	3.11	3	25	9	104
L110N 55+25W	.1	4	5	9	33	32	3.38	2	23	11	112
L110N 55+50W	.2	5	20	9	33	31	3.45	1	17	13	110
L110N 57+25W	.3	ND	15	17	43	286	3.97	1	35	12	175
L110N 58+00W	.2	ND	20	12	39	368	3.46	2	30	12	147
L110N 58+25W	.3	8	10	8	30	288	3.37	3	23	12	158
L110N 58+50W	.2	9	30	10	28	100	3.00	2	18	10	129
L110N 58+75W	.1	12	10	10	30	102	3.05	1	20	10	127
L110N 59+00W	.1	8	5	9	25	74	3.09	1	16	11	214
L110N 59+25W	.4	8	20	10	24	113	2.88	4	16	13	117
L110N 59+50W	.5	10	15	12	26	159	3.34	4	18	15	141
L110N 59+75W	.5	13	15	11	25	135	3.05	3	18	12	130
L110N 60+00W	.7	10	10	14	31	141	4.25	2	20	14	225
L110N 60+25W	.3	7	15	13	17	268	4.28	3	10	12	168
L110N 60+50W	.2	3	25	13	17	320	4.43	3	10	12	177
L110N 60+75W	.2	8	15	13	27	176	3.69	2	23	10	148
L110N 61+00W	.2	6	45	14	26	304	4.01	4	19	10	67
L110N 61+25W	.7	ND	30	12	21	534	4.62	3	15	31	202
L110N 61+50W	.5	ND	60	12	19	692	4.41	3	16	26	176
L110N 61+75W	.1	ND	30	9	17	287	4.29	1	9	8	67
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU #PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L110N 62+00W	.1	ND	40	11	18	217	3.72	2	16	13	75
L110N 62+25W	.1	ND	30	13	21	229	4.23	2	19	12	89
L110N 62+50W	.1	ND	20	13	23	150	3.88	ND	22	9	137
L110N 62+75W	.2	ND	65	15	13	336	4.95	1	12	11	95
L110N 63+00W	.1	ND	60	12	13	262	4.29	1	11	11	83
L110N 63+25W	.1	ND	65	14	17	385	4.89	1	16	12	94
L110N 63+50W	.2	ND	35	15	19	199	4.71	1	18	8	97
L110N 63+75W	.1	ND	35	12	21	209	3.87	1	20	11	66
L110N 64+00W	.1	ND	25	15	15	228	4.55	ND	13	10	102
L110N 64+25W	.2	ND	20	14	14	264	5.18	1	11	10	88
L110N 64+50W	.1	ND	10	14	16	345	4.31	ND	14	11	127
L110N 64+75W	.1	ND	15	14	17	357	4.34	ND	15	11	117
L110N 65+00W	.2	4	25	9	17	152	3.39	1	12	12	106
L110N 65+25W	.3	ND	40	11	22	218	3.95	1	17	12	105
L110N 65+50W	.2	4	25	10	22	138	4.23	1	12	15	142
L110N 65+75W	.3	5	50	8	13	95	3.16	1	8	14	95
L110N 66+00W	.3	5	40	8	12	98	2.98	1	6	13	90
L110N 66+25W	.2	ND	25	10	16	197	3.65	1	11	13	169
L110N 66+50W	.2	3	25	10	17	276	3.91	1	14	12	154
L110N 66+75W	.4	3	25	9	17	302	3.63	2	17	11	75
L110N 67+00W	.3	8	40	9	16	264	3.44	1	10	12	66
L110N 67+25W	.3	5	25	12	17	416	3.89	1	10	13	63
L110N 67+50W	.3	7	20	12	19	396	4.15	1	11	13	68
L110N 67+75W	.2	4	45	12	19	373	4.00	1	12	12	61
L110N 68+00W	.3	3	105	12	20	336	4.15	1	9	12	63
L110N 68+25W	.3	3	30	12	19	376	4.08	1	11	11	61
L110N 68+50W	.3	3	70	10	20	285	4.12	1	10	12	51
L110N 68+75W	.9	ND	45	12	19	268	3.78	1	17	18	142
L110N 69+00W	.4	ND	45	12	18	501	3.98	1	12	15	89
L110N 69+25W	.3	ND	85	14	18	688	4.02	2	13	13	90
L110N 69+50W	.4	ND	40	15	21	316	4.37	1	18	13	208
L110N 69+75W	.3	4	30	9	16	192	3.15	1	8	12	99
L110N 70+00W	.3	3	35	10	17	316	3.62	1	9	12	71
L112N 50+00W	.2	7	5	11	36	32	3.01	1	16	14	60
L112N 50+25W	.3	8	15	11	37	33	3.04	1	17	14	62
L112N 50+50W	.3	3	5	10	32	33	2.73	1	19	12	47
L112N 50+75W	.3	6	30	12	44	41	3.28	1	20	13	46
L112N 51+00W	.2	6	10	11	40	60	3.00	1	22	13	48
L112N 51+25W	.2	ND	15	13	47	95	3.50	1	32	15	56
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE Z	MO PPM	NI PPM	PB PPM	ZN PPM
L112N 51+50W	.1	4	15	17	48	143	3.85	ND	36	15	69
L112N 51+75W	.1	7	ND	14	44	106	3.53	ND	31	11	60
L112N 52+00W	.2	7	10	9	32	32	2.85	ND	15	12	64
L112N 52+25W	.2	4	5	11	42	38	3.39	ND	23	11	58
L112N 52+50W	.3	4	5	15	41	108	3.88	ND	29	13	62
L112N 52+75W	.3	5	5	13	41	90	3.64	ND	26	11	56
L112N 53+00W	.3	3	5	11	34	44	3.19	ND	23	11	53
L112N 53+25W	.1	10	5	7	27	15	2.24	ND	15	11	71
L112N 53+50W	.1	ND	5	10	31	30	2.97	1	22	11	71
L112N 53+75W	.1	6	5	9	31	28	2.99	ND	20	9	69
L112N 54+00W	.1	5	5	11	32	55	3.14	1	21	8	67
L112N 54+25W	.1	5	10	11	32	74	3.12	1	22	12	66
L112N 54+50W	.1	7	ND	13	32	149	3.34	ND	25	12	79
L112N 54+75W	.1	ND	ND	13	34	154	3.43	ND	27	11	81
L112N 55+00W	.1	ND	10	13	34	77	3.80	ND	25	13	98
L112N 55+25W	.2	ND	10	13	34	75	3.65	ND	25	15	94
L112N 55+50W	.4	ND	10	17	40	545	4.37	3	36	18	67
L112N 56+25W	.4	ND	15	13	30	66	3.73	1	21	19	143
L112N 56+50W	.5	ND	10	14	30	98	3.73	1	23	21	131
L112N 56+75W	.3	3	5	10	29	61	3.56	1	27	20	141
L112N 57+00W	.2	ND	ND	15	31	122	3.50	1	27	14	89
L112N 57+25W	.4	ND	ND	15	36	86	3.80	ND	43	13	177
L112N 57+50W	.2	4	ND	10	25	60	3.12	1	18	18	126
L112N 57+75W	.3	ND	ND	10	28	48	3.54	ND	21	16	198
L112N 58+00W	.3	3	5	10	22	44	3.16	1	14	15	177
L112N 58+50W	.5	9	5	9	23	118	3.79	3	12	17	89
L112N 58+75W	.1	3	5	14	25	150	4.07	2	21	14	193
L112N 59+00W	.1	ND	5	14	30	216	3.91	1	28	11	147
L112N 60+75W	.2	ND	25	15	26	336	4.06	1	22	17	142
L112N 61+00W	.2	3	15	16	26	313	4.08	1	22	22	144
L112N 61+25W	.1	8	35	15	24	301	3.95	1	19	16	120
L112N 61+50W	1.2	ND	10	10	23	81	3.32	1	18	19	267
L112N 61+75W	.3	7	5	8	23	60	3.03	2	15	28	152
L112N 62+00W	.1	ND	5	12	26	227	4.27	ND	23	13	160
L112N 62+25W	.1	ND	30	12	27	238	4.41	ND	24	15	175
L112N 62+50W	.1	ND	50	10	19	376	4.39	2	11	16	116
L112N 62+75W	.1	ND	35	12	19	385	4.46	1	12	13	119
L112N 63+00W	.2	ND	100	12	21	297	4.54	1	16	11	170
L112N 63+25W	.2	ND	25	10	18	225	3.85	1	12	14	134
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L112N 63+50W	.1	ND	30	11	19	250	4.04	2	15	12	148
L112N 63+75W	.1	ND	ND	17	18	560	4.94	1	16	16	165
L112N 64+00W	.1	3	10	12	18	107	3.99	1	13	12	216
L112N 64+25W	.1	3	25	14	19	254	3.89	1	13	12	190
L112N 64+50W	.3	4	10	10	16	220	3.87	3	9	10	96
L112N 64+75W	.1	5	25	13	16	327	4.11	3	12	11	128
L112N 65+00W	.5	6	30	11	15	125	3.72	2	10	15	163
L112N 65+25W	.5	4	15	13	16	164	3.82	2	12	13	177
L112N 65+50W	.1	9	25	12	19	227	3.86	1	15	9	77
L112N 65+75W	.1	ND	20	12	19	303	3.90	1	19	10	109
L112N 66+00W	.3	ND	25	13	18	298	4.59	1	13	13	156
L112N 66+25W	.3	ND	10	14	17	413	4.59	1	12	11	99
L112N 66+50W	.3	ND	25	14	18	440	4.48	1	15	14	100
L112N 66+75W	.3	ND	15	11	17	138	3.96	1	11	12	120
L112N 67+25W	.3	ND	5	11	16	134	4.02	ND	11	10	172
L112N 67+50W	.3	12	25	12	19	147	3.74	1	11	12	68
L112N 67+75W	.3	11	15	11	18	145	3.61	1	11	14	62
L112N 68+25W	.3	8	30	13	24	192	3.50	1	14	16	65
L112N 68+50W	.7	13	30	8	15	46	2.64	1	8	16	91
L112N 69+00W	.3	4	20	10	19	170	3.12	1	13	13	125
L112N 69+25W	.3	169	75	30	32	613	6.14	19	32	13	90
L112N 69+50W	.3	197	80	30	32	590	6.52	17	26	13	79
L112N 69+75W	.3	5	15	21	23	276	4.31	3	17	14	171
L112N 70+00W	.5	ND	25	17	25	924	4.78	1	27	11	172
L114N 50+25W	.5	10	5	8	35	48	3.05	1	13	14	56
L114N 50+75W	.1	ND	5	13	44	78	3.71	ND	26	10	93
L114N 51+00W	.1	ND	15	13	40	95	3.53	1	32	9	64
L114N 51+25W	.1	ND	5	13	41	94	3.55	ND	34	12	63
L114N 51+50W	.3	ND	5	12	35	235	3.64	2	20	13	93
L114N 51+75W	.3	ND	10	13	37	393	3.78	ND	25	13	85
L114N 52+00W	.3	ND	10	12	44	298	3.83	ND	26	10	62
L114N 52+25W	1.1	ND	120	11	17	660	4.59	ND	11	24	148
L114N 52+50W	.6	ND	15	14	32	139	3.68	2	34	18	96
L114N 52+75W	.1	ND	5	13	39	116	3.87	ND	35	11	107
L114N 53+00W	.1	ND	ND	12	36	113	3.61	ND	32	11	102
L114N 53+25W	.5	ND	25	11	22	323	3.34	1	16	14	96
L114N 53+50W	.3	ND	10	12	35	46	3.39	ND	27	11	130
L114N 53+75W	.3	ND	5	11	36	27	3.43	ND	21	12	100
L114N 54+00W	.1	ND	10	14	34	132	3.56	1	29	10	89
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L114N 54+25W	.3	5	5	13	30	61	3.41	4	20	11	111
L114N 54+50W	.1	ND	10	12	33	39	3.26	2	22	7	101
L114N 54+75W	.1	ND	5	12	35	31	3.53	1	26	4	81
L114N 55+00W	.1	ND	ND	10	33	67	3.35	1	21	7	99
L114N 55+25W	.1	ND	ND	8	26	45	2.89	1	12	6	113
L114N 55+50W	.1	ND	15	12	34	42	3.60	ND	21	8	88
L114N 55+75W	.1	ND	5	14	37	53	3.91	1	25	6	96
L114N 56+00W	.1	ND	5	12	35	57	3.51	1	24	10	79
L114N 56+25W	.1	ND	10	10	28	34	3.40	1	11	8	97
L114N 56+50W	.1	ND	5	14	33	213	4.14	1	25	7	104
L114N 56+75W	.1	ND	5	13	37	59	3.72	ND	30	8	111
L114N 57+00W	.1	ND	5	11	30	64	3.31	ND	24	7	130
L114N 57+25W	.1	ND	25	11	31	85	3.39	1	18	8	111
L114N 57+50W	.1	ND	10	12	28	69	3.73	ND	17	11	158
L114N 57+75W	.1	ND	25	20	35	135	5.00	ND	29	12	161
L114N 58+00W	.1	8	20	19	28	197	4.86	1	23	8	114
L114N 58+25W	.1	ND	10	17	38	103	4.85	1	27	13	114
L114N 58+50W	.1	ND	10	14	32	88	4.35	1	25	11	114
L114N 58+75W	.1	ND	5	11	28	48	3.82	ND	19	9	94
L114N 59+00W	.1	ND	5	15	32	94	4.19	ND	26	9	114
L114N 59+25W	.1	ND	ND	15	30	81	4.22	ND	26	9	116
L114N 59+50W	.1	ND	ND	14	26	258	4.89	1	20	10	110
L114N 59+75W	.1	ND	5	14	26	267	5.03	1	19	12	113
L114N 60+00W	.1	10	10	13	24	165	4.39	2	11	14	77
L114N 60+25W	.1	10	30	12	22	156	4.27	1	11	12	75
L114N 60+50W	.1	7	5	14	28	239	4.12	2	21	11	92
L114N 60+75W	.1	8	5	16	30	64	4.64	2	19	11	198
L114N 61+00W	.1	10	10	15	29	54	4.36	2	17	8	181
L114N 61+25W	.1	10	5	13	27	56	4.07	1	20	9	123
L114N 61+50W	.1	38	ND	16	15	72	5.35	3	9	8	104
L114N 61+75W	.1	ND	10	10	26	41	3.38	1	21	7	138
L114N 62+00W	.1	70	15	37	22	358	11.76	19	25	6	60
L114N 62+25W	.1	14	10	34	50	159	5.57	3	233	7	99
L114N 62+50W	.1	16	5	14	21	68	3.68	2	14	17	168
L114N 62+75W	.1	8	5	8	25	65	3.54	1	15	20	117
L114N 63+00W	.7	7	25	6	19	101	3.07	1	9	19	83
L114N 63+25W	.7	4	15	12	21	108	3.67	1	15	18	186
L114N 63+50W	.9	11	5	5	15	20	1.99	2	6	15	79
L114N 64+00W	.1	4	25	11	22	115	3.95	1	14	12	198
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L114N 64+25W	.1	8	ND	10	20	71	3.42	1	11	16	146
L114N 64+75W	.3	6	20	9	20	142	3.30	1	13	16	146
L114N 65+00W	.4	11	25	7	13	73	2.20	1	8	16	113
L114N 65+25W	.1	5	30	12	21	191	3.78	1	14	16	172
L114N 65+50W	.3	5	15	13	22	198	4.02	1	17	17	189
L114N 65+75W	.5	10	20	11	17	90	3.19	2	10	17	173
L114N 66+00W	.3	8	35	14	18	263	3.51	1	13	18	164
L114N 66+25W	.1	9	20	14	22	377	4.16	2	15	14	102
L114N 66+50W	.2	12	10	11	17	123	3.52	2	9	17	108
L114N 66+75W	.4	9	10	13	17	132	3.57	1	10	15	144
L114N 67+00W	.1	ND	30	14	22	231	4.42	2	13	13	102
L114N 67+25W	.1	ND	20	12	20	162	4.41	ND	15	11	119
L114N 67+50W	.1	3	35	10	17	95	4.23	1	6	10	95
L114N 67+75W	.1	ND	25	14	17	150	3.97	1	7	13	117
L114N 68+25W	.1	ND	15	9	15	72	3.07	ND	5	8	99
L114N 68+50W	.1	ND	15	11	16	94	3.53	ND	8	9	109
L114N 68+75W	.7	8	40	8	12	239	2.61	1	6	9	37
L114N 69+00W	.1	ND	60	14	20	471	4.27	1	15	8	71
L114N 69+25W	.1	3	40	14	19	438	4.24	1	15	7	66
L114N 69+50W	.3	ND	35	13	20	366	4.46	1	17	8	60
L114N 69+75W	.3	9	15	7	19	35	3.75	2	6	10	69
L118N 46+75W	.2	ND	5	14	44	81	3.52	1	25	10	75
L118N 47+00W	.2	6	5	13	38	52	3.18	1	20	9	53
L118N 47+25W	.4	5	5	13	42	70	3.41	1	25	12	63
L118N 47+50W	.1	ND	15	14	45	95	3.57	1	24	9	57
L118N 47+75W	.1	3	5	12	54	201	3.46	1	27	8	82
L118N 48+00W	.1	ND	10	18	66	838	4.36	1	40	6	97
L118N 48+25W	.1	ND	15	16	69	603	4.26	1	33	7	60
L118N 48+50W	.1	ND	5	10	31	196	3.63	1	11	21	135
L118N 48+75W	.2	ND	15	17	28	813	5.16	1	12	7	176
L118N 49+00W	.1	4	10	15	44	114	4.36	1	16	11	120
L118N 49+25W	.1	ND	5	17	68	302	4.66	1	43	7	80
L118N 49+50W	.1	ND	5	19	67	336	4.61	ND	38	7	68
L118N 49+75W	.1	5	10	8	25	52	2.93	2	8	13	139
L118N 50+00W	.1	ND	5	14	69	39	4.48	1	24	10	87
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1



VANGEOCHEM LAB LIMITED

MAIN OFFICE
1521 PEMBERTON AVE.
NORTH VANCOUVER, B.C. V7P 2S3
(604) 986-5211 TELEX: 04-352578

BRANCH OFFICE
1630 PANDORA ST.
VANCOUVER, B.C. V5L 1L6
(604) 251-5656

*F. U.
Paul Stanley*

M. J. ✓

*Mark
Tindal*

ASSAY ANALYTICAL REPORT

CLIENT: MASCOT GOLD MINES LTD.
ADDRESS: 1440 - 800 W. Pender St.
: Vancouver, B.C.
: V6C 2V6

DATE: Sept 16 1986

REPORT#: 860464 AA
JOB#: 860464

PROJECT#: 5061 - Cariboo Bell
SAMPLES ARRIVED: Sept 16 1986
REPORT COMPLETED: Sept 16 1986
ANALYSED FOR: W

INVOICE#: 860464 NA
TOTAL SAMPLES: 3
REJECTS/PULPS: 90 DAYS/1 YR
SAMPLE TYPE: 3 ROCK PULP

SAMPLES FROM: VGC file 860411
COPY SENT TO: MASCOT GOLD MINES LTD.

PREPARED FOR: MASCOT GOLD MINES LTD.

ANALYSED BY: David Chiu

SIGNED: _____

Registered Provincial Assayer

GENERAL REMARK: None



VANGEOCHEM LAB LIMITED

MAIN OFFICE
1521 PEMBERTON AVE.
NORTH VANCOUVER, B.C. V7P 2S3
(604) 986-5211 TELEX: 04-352578

BRANCH OFFICE
1630 PANDORA ST.
VANCOUVER, B.C. V5L 1L6
(604) 251-5656

REPORT NUMBER: 860464 AA

JOB NUMBER: 860464

MASCOT GOLD MINES LTD.

PAGE 1 OF 1

SAMPLE #	W %
86-MR-007	.28
86-MR-008	.02
86-MR-009	<.01

DETECTION LIMIT

1 Troy oz/short ton = 34.28 ppm

.01

1 ppm = 0.0001%

ppm = parts per million

< = less than

signed: _____

VANGEOCHEM LAB LIMITED

MAIN OFFICE: 1521 PEMBERTON AVE. N.VANCOUVER B.C. V7P 2S3 PH: (604)986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND
 IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE, ND= NOT DETECTED, -= NOT ANALYZED. *AU= GEOCHEM

COMPANY: E & B EXPLORATIONS
 ATTENTION:
 PROJECT: 5061-CB PO#5589

REPORT#: 860435PA DATE RECEIVED: 86/09/03
 JOB#: 860435 DATE COMPLETED: 86/09/16
 INVOICE#: 860435NA COPY SENT TO:

ANALYST W. Raves

PAGE 1 OF 1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L96N 46+25W	.1	5	15	9	27	89	2.80	3	18	13	58
L112N 44+00W	.1	ND	10	12	36	62	2.68	1	24	12	60
L112N 44+25W	.1	ND	5	11	49	24	3.35	ND	23	11	82
L112N 44+50W	.3	3	5	9	26	23	2.35	ND	14	9	44
L112N 44+75W	.1	ND	5	13	40	53	3.20	ND	25	13	56
L112N 45+00W	.1	ND	20	10	40	39	3.10	ND	24	14	52
L112N 45+25W	.2	ND	10	10	53	34	3.28	ND	24	12	56
L112N 45+50W	.3	ND	5	10	52	34	3.38	ND	24	14	66
L112N 45+75W	.2	ND	5	10	52	35	3.27	ND	23	13	57
L112N 46+00W	.2	ND	5	10	49	28	3.10	ND	23	12	51
L112N 46+25W	.3	5	15	11	44	30	3.05	ND	23	13	46
L112N 46+50W	.1	3	10	9	37	29	2.81	ND	23	12	58
L112N 46+75W	.5	3	10	8	30	27	2.70	1	21	15	64
L112N 47+00W	.3	4	5	9	36	27	2.53	ND	20	13	51
L112N 47+25W	.3	4	5	10	39	33	2.77	ND	22	14	50
L112N 47+50W	.2	4	10	11	47	37	3.26	ND	26	15	57
L112N 47+75W	.2	ND	5	10	44	25	3.26	1	23	15	69
L112N 48+00W	.1	8	5	17	67	116	4.15	ND	48	19	61
L112N 48+25W	.1	3	10	9	31	22	2.75	1	24	15	61
L112N 48+50W	.3	ND	20	13	50	42	3.60	1	36	16	64
L112N 48+75W	.3	ND	15	10	38	25	2.95	1	23	16	72
L112N 49+00W	.3	4	5	9	30	44	2.85	ND	20	15	63
L112N 49+25W	.2	ND	5	13	42	63	3.63	1	25	16	55
L112N 49+50W	.3	ND	5	8	31	15	2.57	ND	20	16	68
L112N 49+75W	.4	3	5	11	42	25	3.02	1	23	16	69
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

VANGEOCHEM LAB LIMITED

MAIN OFFICE: 1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604)986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE. ND= NOT DETECTED. -= NOT ANALYZED. *AU= AQUA REGA/AAS

COMPANY: E & B EXPLORATIONS REPORT#: 860434PA DATE RECEIVED: 86/09/03
 ATTENTION: L. SALEKEN & M. TINDALL JOB#: 860434 DATE COMPLETED: 860/09/22
 PROJECT: 5061-CB PO#5589 INVOICE#: 860434NA COPY SENT TO: VANCOUVER OFFICE

ANALYST W. Burns

PAGE 1 OF 8

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L106N 70+25W	.1	ND	35	19	30	408	4.67	2	22	15	111
L106N 70+50W	.1	ND	20	50	62	1330	7.18	7	48	38	264
L106N 70+75W	.1	ND	15	15	28	322	4.01	1	19	15	107
L106N 71+00W	.1	7	5	5	22	57	3.13	1	5	4	51
L106N 71+25W	.1	ND	30	11	27	153	4.15	ND	17	10	119
L106N 71+50W	.1	ND	30	16	27	405	4.77	1	16	14	102
L106N 71+75W	.1	3	30	9	21	111	3.54	1	8	13	103
L106N 72+00W	.1	ND	30	12	23	199	3.77	1	13	15	116
L106N 72+25W	.1	8	35	20	24	633	4.75	1	21	19	119
L106N 72+50W	.1	ND	30	18	30	405	4.32	1	20	16	99
L106N 72+75W	.1	3	20	16	29	356	4.25	2	18	18	94
L106N 73+00W	.1	ND	5	11	23	282	2.15	ND	14	13	62
L108N 70+25W	.1	ND	25	22	28	448	4.90	3	19	12	116
L108N 70+50W	.1	ND	15	12	23	92	3.87	1	11	11	231
L108N 70+75W	.1	8	10	6	20	43	3.12	1	6	10	92
L108N 71+00W	.1	ND	5	10	21	121	4.12	ND	10	8	171
L108N 71+25W	.1	ND	15	12	22	61	5.12	ND	7	9	138
L108N 71+50W	.1	ND	40	22	24	763	4.95	2	20	16	113
L108N 71+75W	.1	3	20	16	24	455	4.10	1	16	15	99
L108N 72+00W	.1	10	50	13	21	354	3.83	1	14	13	89
L108N 72+25W	.1	6	15	14	24	233	3.85	2	20	18	78
L108N 72+50W	.1	7	30	12	27	210	3.47	1	18	16	85
L108N 72+75W	.1	9	20	14	26	296	3.70	1	18	20	84
L108N 73+00W	.1	5	10	13	25	293	3.62	1	15	17	82
L108N 73+25W	.1	7	20	13	29	135	2.62	1	17	20	66
L108N 73+50W	.1	11	10	12	27	57	2.97	1	16	14	66
L108N 73+75W	.1	14	10	6	19	43	2.11	1	9	15	55
L108N 74+00W	.1	10	15	6	15	59	1.63	ND	8	19	45
L110N 70+25W	.1	3	5	9	27	157	2.38	ND	15	15	57
L110N 70+50W	.1	ND	20	12	23	375	3.59	1	15	13	130
L110N 70+75W	.1	ND	20	10	25	3150	3.24	2	24	2	78
L110N 71+00W	.1	ND	5	9	29	187	3.41	ND	12	4	155
L110N 71+25W	.1	ND	20	11	24	140	4.54	2	10	7	176
L110N 71+50W	.1	ND	25	7	24	4061	2.52	2	20	ND	60
L110N 71+75W	.1	ND	15	23	40	2914	5.48	2	38	16	136
L110N 72+00W	.1	ND	10	8	20	1820	2.54	1	16	ND	62
L110N 72+25W	.1	ND	20	16	29	273	5.12	ND	17	13	254
L110N 72+50W	.1	ND	20	12	30	147	4.99	ND	12	9	222
L110N 72+75W	.1	5	30	12	24	207	4.25	2	13	12	106
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L110N 73+00W	.1	ND	ND	28	34	903	5.41	2	27	30	163
L110N 73+25W	.1	5	145	18	29	465	5.09	1	23	23	121
L110N 73+50W	.1	ND	20	13	27	270	5.37	2	17	18	167
L110N 73+75W	.1	ND	10	20	31	398	4.29	4	16	18	177
L110N 74+00W	.1	5	5	18	27	305	4.99	3	15	19	146
L112N 70+25W	.1	ND	25	16	27	487	5.30	2	16	16	164
L112N 70+50W	.1	ND	20	20	27	1129	4.65	2	22	15	123
L112N 70+75W	.1	ND	15	15	25	416	5.33	1	16	13	151
L112N 71+00W	.1	4	5	12	20	1273	3.45	4	18	7	93
L112N 71+25W	.1	ND	20	23	33	1127	5.58	2	27	19	154
L112N 71+50W	.1	ND	15	13	31	2268	4.01	1	31	15	98
L112N 71+75W	.1	ND	15	27	52	1572	6.50	3	46	29	189
L112N 72+00W	.1	ND	20	15	36	455	4.25	1	28	14	142
L112N 72+25W	.1	ND	20	16	38	466	4.54	1	30	15	143
L112N 72+50W	.1	ND	10	9	31	299	3.24	1	24	6	116
L112N 72+75W	.1	4	30	16	44	468	3.72	2	25	13	76
L112N 73+00W	.1	4	25	10	29	234	4.07	1	11	13	117
L112N 73+25W	.1	ND	20	11	28	165	4.74	1	10	13	172
L112N 73+50W	.1	4	20	3	13	2102	1.60	3	14	ND	31
L112N 73+75W	.1	4	20	3	14	1911	1.58	3	20	ND	32
L112N 74+00W	.1	ND	10	12	30	177	4.89	4	23	14	192
L114N 44+75W	.1	ND	5	11	38	84	3.15	ND	26	8	60
L114N 45+00W	.1	ND	5	11	51	42	3.77	ND	22	7	78
L114N 45+25W	.1	ND	ND	14	63	45	4.02	ND	30	10	93
L114N 45+50W	.1	ND	ND	13	68	36	4.10	ND	29	7	103
L114N 45+75W	.1	ND	ND	12	78	45	4.34	ND	30	11	79
L114N 46+00W	.1	ND	ND	14	90	52	4.87	ND	33	9	69
L114N 46+25W	.1	ND	ND	14	71	49	4.27	ND	30	11	75
L114N 46+50W	.1	ND	ND	14	67	58	4.55	ND	29	12	66
L114N 46+75W	.1	14	10	11	28	158	3.22	1	19	17	56
L114N 47+00W	.1	5	10	11	45	79	3.40	ND	24	9	66
L114N 47+25W	.1	ND	5	10	63	26	3.70	ND	21	8	102
L114N 47+50W	.1	ND	10	12	67	44	3.83	ND	34	12	77
L114N 47+75W	.1	4	5	8	50	30	3.11	ND	18	12	59
L114N 48+00W	.1	21	5	6	30	13	2.12	2	12	24	44
L114N 48+25W	.1	5	5	15	62	80	3.77	ND	42	32	76
L114N 48+50W	.1	11	5	12	41	100	3.32	1	23	30	95
L114N 48+75W	.8	14	190	29	22	5302	4.67	9	14	50	232
L114N 49+00W	.2	10	100	25	34	2768	5.22	6	22	39	194
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L114N 49+25W	.4	7	20	15	44	318	3.88	2	25	17	89
L114N 49+50W	.1	ND	15	12	46	137	3.52	1	26	15	61
L114N 49+75W	.1	8	10	10	36	100	3.08	1	19	16	79
L114N 70+25W	.4	ND	5	12	27	1366	3.31	2	26	15	86
L114N 70+50W	.1	ND	35	12	22	372	3.92	1	20	14	106
L114N 70+75W	.1	4	35	13	18	371	3.80	1	12	16	93
L114N 71+00W	.1	ND	20	11	19	254	3.87	1	12	14	162
L114N 71+50W	.1	ND	25	14	23	494	4.02	1	17	12	138
L114N 71+75W	.1	ND	20	12	22	405	4.00	1	14	13	119
L114N 72+00W	.1	3	55	16	24	650	4.25	1	18	11	75
L114N 72+25W	.1	ND	40	16	24	560	3.90	1	19	14	92
L114N 72+50W	.1	ND	35	19	28	812	4.50	2	21	14	96
L114N 72+75W	.1	4	45	17	27	661	4.34	2	21	13	72
L114N 73+00W	.1	3	25	13	23	1235	3.55	4	18	10	77
L114N 73+25W	.1	ND	15	15	25	1598	3.59	3	22	9	101
L114N 73+50W	.1	ND	15	18	33	1023	4.62	2	25	11	112
L114N 73+75W	.1	ND	15	15	23	702	3.65	3	20	11	121
L114N 74+00W	.1	ND	20	13	23	799	3.46	2	17	7	127
L116N 45+75W	.1	7	10	17	39	109	3.83	1	25	10	67
L116N 46+00W	.1	6	5	11	34	449	2.77	1	29	7	81
L116N 46+25W	.1	4	5	13	38	56	3.31	1	28	14	69
L116N 46+50W	.1	9	10	12	30	83	3.01	1	22	13	51
L116N 46+75W	.1	4	5	12	51	22	3.54	1	20	13	86
L116N 47+00W	.1	ND	5	15	70	43	4.23	ND	34	10	68
L116N 47+25W	.1	ND	5	15	69	41	4.49	ND	34	10	75
L116N 47+50W	.1	ND	5	16	63	64	4.30	ND	29	11	78
L116N 47+75W	.1	ND	5	11	48	32	3.60	ND	26	12	86
L116N 48+00W	.1	ND	5	16	45	34	3.87	ND	30	16	97
L116N 48+25W	.1	ND	10	14	57	49	3.93	ND	30	12	82
L116N 48+50W	.1	ND	5	13	52	36	3.85	ND	27	10	69
L116N 48+75W	.1	4	ND	9	43	23	3.20	1	16	15	89
L116N 49+00W	.1	ND	30	23	47	1123	5.95	1	37	11	145
L116N 49+25W	.1	4	10	17	42	1198	4.57	ND	27	13	120
L116N 49+50W	.1	ND	5	13	52	162	3.87	ND	28	12	101
L116N 49+75W	.1	6	10	21	42	939	5.37	2	24	19	161
L116N 50+00W	.1	3	15	18	41	464	4.59	ND	27	19	120
L116N 50+25W	.1	ND	5	14	48	73	3.97	ND	29	14	135
L116N 50+50W	.1	46	25	36	22	1276	6.31	3	19	60	99
L116N 50+75W	.1	ND	25	14	45	516	4.19	ND	30	14	169
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU PPM	CO PPM	CR PPM	CU PPM	FE I	MG PPM	NI PPM	PB PPM	ZN PPM
L116N 51+00W	.1	15	ND	9	16	190	3.52	2	6	23	136
L116N 51+25W	.1	9	ND	10	41	28	3.43	1	15	12	121
L116N 51+50W	.1	11	ND	9	45	26	3.41	1	15	11	96
L116N 51+75W	.1	5	ND	13	52	75	4.36	1	21	12	98
L116N 52+00W	.1	ND	20	24	48	604	5.92	ND	37	15	108
L116N 52+25W	.1	ND	5	20	56	822	4.93	ND	45	13	121
L116N 52+50W	.1	13	30	18	37	509	4.94	5	20	58	94
L116N 52+75W	.1	ND	ND	15	42	168	4.20	ND	38	6	109
L116N 53+00W	.1	ND	ND	13	38	104	4.20	ND	29	12	162
L116N 53+25W	.1	3	ND	14	52	144	3.78	1	88	12	96
L116N 53+50W	.1	9	ND	8	30	33	2.95	1	16	13	85
L116N 53+75W	.1	25	60	31	28	695	7.84	16	49	18	209
L116N 54+00W	.1	16	40	16	33	464	4.94	6	21	17	139
L116N 54+25W	.1	ND	20	14	32	259	3.89	1	24	21	332
L116N 54+50W	.1	ND	20	20	40	151	4.84	ND	32	35	237
L116N 54+75W	.1	ND	5	13	43	69	3.81	ND	31	11	140
L116N 55+00W	.4	ND	15	15	49	177	4.63	ND	33	14	142
L116N 55+25W	.1	ND	25	17	44	449	4.51	1	34	15	130
L116N 55+50W	.1	ND	20	18	43	382	4.65	ND	38	9	93
L116N 55+75W	.1	5	10	13	27	133	4.25	1	19	14	177
L116N 56+00W	.3	ND	15	21	47	546	5.03	ND	40	16	152
L116N 56+25W	.1	ND	20	14	36	218	4.62	ND	23	16	143
L116N 56+50W	.1	ND	5	13	33	170	4.90	1	18	18	175
L116N 56+75W	.1	ND	5	23	15	379	4.68	4	13	12	301
L116N 57+25W	.1	ND	5	14	39	147	5.19	1	20	45	265
L116N 57+50W	.1	6	15	11	25	185	4.16	1	12	22	170
L116N 57+75W	.1	3	10	8	25	95	3.91	2	9	17	149
L116N 58+00W	.1	4	10	29	18	131	3.98	1	10	21	275
L118N 50+50W	.1	3	15	13	42	119	4.27	1	21	16	86
L118N 51+00W	.1	ND	10	15	54	128	4.95	1	25	18	135
L118N 51+25W	.1	ND	10	15	45	140	4.48	1	26	18	148
L118N 51+50W	.1	ND	10	18	62	345	4.80	1	36	17	120
L118N 51+75W	.1	ND	15	16	63	952	5.00	ND	38	35	109
L118N 52+00W	.1	ND	5	16	60	1031	5.03	ND	39	33	114
L118N 52+25W	.1	ND	10	17	83	109	4.88	ND	40	13	72
L118N 52+50W	.1	ND	5	16	65	53	4.56	ND	41	8	96
L118N 52+75W	.1	ND	15	21	77	113	4.94	ND	50	12	78
L118N 53+00W	.1	ND	5	12	52	30	3.61	ND	26	14	128
L118N 53+25W	.1	4	5	22	66	224	4.67	4	60	23	92
DETECTION LIMIT	.1	3	45	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L118N 53+50W	.1	32	15	34	65	378	6.18	8	178	50	122
L118N 53+75W	.1	ND	10	20	64	248	4.81	2	62	24	300
L118N 54+00W	.1	ND	5	16	54	126	4.61	3	32	14	78
L118N 54+25W	.1	ND	10	14	46	90	3.85	1	31	13	84
L118N 54+50W	.1	6	5	11	39	48	3.35	ND	25	12	107
L118N 54+75W	.1	ND	5	18	82	125	5.01	ND	47	13	80
L118N 55+00W	.1	ND	5	14	57	125	4.26	ND	40	12	124
L118N 55+25W	.1	5	5	15	50	157	4.23	1	29	14	114
L118N 55+50W	.1	5	35	18	57	162	4.51	1	35	16	98
L118N 55+75W	.1	5	15	16	48	124	4.10	1	26	13	100
L118N 56+00W	.1	4	15	12	43	107	4.24	1	21	12	120
L118N 56+25W	.1	ND	15	15	52	138	4.78	ND	34	16	154
L118N 56+50W	.1	ND	25	12	49	139	4.47	1	30	15	134
L118N 56+75W	.1	ND	10	11	46	157	4.29	1	28	9	157
L118N 57+00W	.1	8	5	13	34	142	4.04	1	20	22	87
L118N 57+25W	.1	ND	5	19	82	189	4.66	1	83	12	108
L120N 46+50W	.1	ND	5	19	53	65	4.58	ND	51	19	98
L120N 46+75W	.1	4	5	11	37	45	3.15	ND	31	10	84
L120N 47+00W	.1	5	5	11	37	45	3.06	1	28	13	69
L120N 47+25W	.1	9	10	7	31	29	2.45	1	19	12	57
L120N 47+50W	.1	8	ND	11	49	33	3.16	1	40	12	67
L120N 47+75W	.1	5	ND	10	43	28	2.96	ND	26	12	61
L120N 48+00W	.1	ND	ND	12	56	48	3.72	ND	36	8	73
L120N 48+25W	.1	ND	ND	13	61	51	4.02	ND	36	4	79
L120N 48+50W	.1	ND	5	14	77	43	4.29	ND	35	12	83
L120N 48+75W	.1	ND	20	12	61	47	4.42	ND	32	7	101
L120N 49+00W	.1	6	5	10	45	201	2.97	1	23	13	92
L120N 49+25W	.1	ND	5	14	67	244	4.90	ND	34	13	126
L120N 49+50W	.1	ND	5	21	68	797	4.87	ND	48	6	84
L120N 49+75W	.1	ND	5	19	72	638	4.59	ND	49	11	78
L120N 50+25W	.1	ND	5	18	61	192	4.15	ND	30	9	132
L120N 50+50W	.1	ND	5	16	63	114	4.29	ND	40	8	78
L120N 50+75W	.1	ND	5	18	74	133	4.46	ND	41	8	78
L120N 51+00W	.1	ND	5	19	68	311	4.58	1	44	12	90
L120N 51+25W	.1	ND	5	16	65	109	4.41	1	40	11	114
L120N 51+50W	.1	ND	10	19	73	148	4.92	ND	46	9	104
L120N 51+75W	.1	ND	5	16	71	108	4.58	ND	36	7	115
L120N 52+00W	.1	ND	5	13	63	58	4.31	1	29	5	72
L120N 52+50W	.1	ND	5	15	66	69	3.98	1	50	8	54
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L120N 52+75W	.1	9	5	16	66	54	3.82	1	31	9	51
L120N 53+00W	.1	4	5	13	52	50	3.43	1	32	6	122
L120N 53+50W	.1	ND	5	13	53	49	3.50	1	27	6	134
L120N 53+75W	.1	5	ND	14	60	123	3.72	1	37	9	100
L120N 54+00W	.1	3	ND	18	63	77	4.24	1	36	9	75
L120N 54+25W	.1	4	5	17	73	89	4.16	1	43	11	73
L120N 54+75W	.1	3	10	17	68	59	4.02	1	39	9	58
L120N 55+25W	.1	4	5	18	65	117	4.05	1	38	14	77
L120N 55+50W	.1	9	5	13	49	41	3.37	1	26	10	52
L120N 55+75W	.1	6	5	12	35	47	3.22	2	19	10	58
L120N 57+75W	.1	11	ND	10	45	41	3.12	2	16	12	74
L120N 58+00W	.1	11	ND	9	38	35	2.80	2	14	13	66
L122N 47+25W	.1	9	ND	13	44	85	3.07	1	22	12	56
L122N 47+50W	.1	8	ND	14	47	86	3.29	1	24	12	61
L122N 47+75W	.3	3	ND	13	61	42	3.71	1	25	10	110
L122N 48+00W	.5	4	10	13	60	34	3.60	1	30	10	102
L122N 48+25W	.3	7	10	14	53	33	3.54	1	26	11	67
L122N 48+50W	.1	5	10	12	50	26	3.32	1	30	10	85
L122N 48+75W	.1	9	ND	11	34	38	2.89	1	20	10	53
L122N 49+00W	.5	11	ND	10	41	30	2.95	1	19	12	65
L122N 49+25W	.1	9	ND	12	35	33	2.83	1	25	12	46
L122N 49+50W	.1	9	ND	10	48	31	3.04	1	24	10	63
L122N 49+75W	.3	5	5	15	63	91	3.87	2	35	13	65
L122N 50+00W	.3	ND	5	14	61	191	3.83	1	34	11	97
L122N 50+25W	.1	5	20	14	55	216	3.68	1	25	9	63
L122N 50+50W	.1	9	10	16	58	206	3.86	1	30	11	58
L122N 50+75W	.1	ND	5	13	43	187	3.58	1	31	10	70
L122N 51+00W	.1	5	5	13	42	177	3.58	1	31	10	66
L122N 51+25W	.7	3	10	15	52	346	3.43	ND	40	10	63
L122N 51+50W	.1	6	5	13	56	66	3.71	1	28	12	68
L122N 51+75W	.1	ND	ND	18	63	123	4.05	1	37	13	64
L122N 52+00W	.1	4	ND	14	54	122	3.72	1	31	11	63
L122N 52+25W	.1	ND	ND	20	71	103	4.41	ND	44	10	67
L122N 52+50W	.1	ND	ND	20	67	98	4.40	ND	41	10	111
L122N 52+75W	.1	3	ND	14	63	57	3.97	2	29	10	126
L122N 53+75W	.1	ND	ND	23	55	230	5.01	ND	46	12	142
L122N 54+00W	.1	5	ND	14	49	74	3.85	1	27	11	65
L122N 54+25W	.1	5	ND	17	72	84	4.31	1	34	12	63
L122N 54+50W	.1	ND	ND	12	49	49	3.29	ND	30	6	93
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU +PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L122N 54+75W	.1	5	ND	14	58	47	3.92	1	28	12	68
L122N 55+00W	.1	ND	ND	18	57	77	4.15	ND	54	18	119
L122N 55+25W	.1	ND	ND	18	56	76	4.07	ND	52	18	117
L122N 55+50W	.1	ND	ND	14	62	48	3.75	1	45	16	92
L122N 55+75W	.1	5	ND	16	67	92	4.45	1	42	17	92
L122N 56+00W	.1	3	ND	13	68	43	4.08	1	34	14	86
L122N 56+25W	.1	ND	ND	12	60	48	3.87	1	34	15	100
L122N 56+50W	.1	6	ND	11	58	57	3.82	2	27	15	100
L122N 56+75W	.1	11	ND	7	48	21	2.65	2	15	13	75
L122N 57+00W	.1	16	ND	6	36	14	1.92	2	10	12	58
L122N 57+25W	.1	ND	ND	15	71	55	4.25	1	44	15	82
L122N 57+50W	.1	6	ND	13	65	44	3.79	1	36	12	80
L122N 57+75W	.1	13	ND	9	43	20	2.52	2	14	13	73
L122N 58+00W	.1	6	20	12	47	70	3.67	1	27	19	112
L124N 49+00W	.1	6	20	11	46	32	3.34	1	24	11	86
L124N 49+25W	.1	9	5	11	44	31	3.16	1	23	11	84
L124N 49+50W	.1	8	5	11	46	35	3.13	1	21	10	59
L124N 49+75W	.1	4	5	15	53	45	3.79	1	25	11	66
L124N 50+00W	.1	4	5	14	53	45	3.75	1	26	12	63
L124N 50+25W	.1	8	5	11	42	45	3.04	1	26	13	51
L124N 50+50W	.1	ND	5	16	60	118	4.05	1	33	17	57
L124N 50+75W	.1	ND	10	16	59	256	4.08	ND	40	16	63
L124N 51+00W	.1	ND	5	21	70	265	4.89	ND	45	16	88
L124N 51+25W	.1	ND	10	20	68	250	4.70	ND	45	19	86
L124N 51+50W	.1	8	ND	9	36	23	2.97	1	15	7	55
L124N 51+75W	.1	8	ND	10	34	45	2.70	1	18	5	48
L124N 52+00W	.1	4	ND	11	50	45	3.44	1	20	4	62
L124N 52+25W	.1	5	ND	10	37	67	3.04	1	19	8	57
L124N 52+50W	.1	3	ND	12	44	75	3.45	1	24	7	64
L124N 52+75W	.1	ND	ND	12	41	40	3.25	1	20	3	75
L124N 53+00W	.1	ND	ND	13	46	49	3.66	ND	23	4	65
L124N 53+25W	.1	ND	ND	11	51	49	3.37	1	24	3	70
L124N 53+50W	.1	ND	ND	13	44	108	3.37	ND	24	5	51
L124N 53+75W	.1	ND	ND	16	64	168	4.26	ND	36	3	66
L124N 54+00W	.1	ND	ND	12	57	42	3.83	ND	24	7	105
L124N 55+00W	.1	ND	ND	14	66	56	4.12	ND	30	8	92
L124N 55+25W	.1	ND	ND	12	78	30	4.37	1	29	6	87
L124N 55+50W	.1	ND	10	13	31	112	3.74	ND	19	3	61
L124N 55+75W	.1	ND	10	11	43	150	3.33	ND	26	2	53
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L124N 56+00W	.1	8	ND	9	28	83	2.91	ND	13	1	41
L124N 56+25W	.1	ND	ND	11	48	37	3.59	ND	21	4	72
L124N 56+50W	.1	5	ND	12	42	45	3.59	ND	17	7	51
L124N 56+75W	.1	ND	10	13	61	35	3.69	ND	34	5	60
L124N 57+00W	.1	ND	5	9	25	19	3.37	ND	8	8	77
L124N 57+25W	.1	ND	ND	10	13	15	3.54	ND	6	7	96
L124N 57+50W	.1	ND	15	11	45	31	3.54	ND	19	5	57
L124N 57+75W	.1	ND	ND	9	19	17	3.40	ND	13	4	79
L124N 58+00W	.1	ND	ND	10	47	26	3.47	ND	19	6	46
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

VANGEOCHEM LAB LIMITED

Paul Sterling

M. IN OFFICE: 1521 PEMBERTON AVE. N. VANCOUVER B.C. V7P 2S3 PH: (604)986-5211
 BRANCH OFFICE: 1630 PANDORA ST. VANCOUVER B.C. V5L 1L6 PH: (604)251-5656

ICAP GEOCHEMICAL ANALYSIS

A .5 GRAM SAMPLE IS DIGESTED WITH 5 ML OF 3:1:2 HCL TO HNO3 TO H2O AT 95 DEG. C FOR 90 MINUTES AND IS DILUTED TO 10ML WITH WATER. IS= INSUFFICIENT SAMPLE. ND= NOT DETECTED. -- NOT ANALYZED. *AU= AQUA REGIA/AAS

COMPANY: E & B EXPLORATIONS REPORT#: B60441PA DATE RECEIVED: 86/09/05
 ATTENTION: L.SALEKEN & M.TINDALL JOB#: B60441 DATE COMPLETED: 86/09/24
 PROJECT: 5061-CB PO#5600 INVOICE#: 860441NA COPY SENT TO: VANCOUVER OFFICE

ANALYST W. R. R. S.

PAGE 1 OF 10

SAMPLE NAME	AG PPM	AS PPM	AU +PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L85N 50+25W	.1	3	ND	11	27	38	3.33	1	17	19	230
L85N 50+50W	.1	ND	10	12	32	24	2.65	ND	21	13	249
L85N 50+75W	.3	5	5	15	12	37	2.91	ND	8	13	206
L85N 51+00W	.1	4	10	9	24	30	2.40	ND	17	11	90
L85N 51+25W	.3	9	5	13	15	56	2.90	ND	9	11	136
L85N 51+50W	.1	5	5	13	16	43	2.78	ND	9	11	137
L85N 51+75W	.1	5	10	9	26	20	2.26	ND	13	9	113
L85N 52+00W	.1	3	10	10	30	21	2.36	ND	18	12	129
L85N 52+25W	.1	ND	10	7	22	18	2.21	ND	11	13	103
L85N 52+50W	.1	3	10	12	19	50	2.90	ND	10	12	150
L85N 52+75W	.1	3	20	12	22	62	3.38	ND	12	11	140
L85N 53+00W	.1	3	20	12	19	58	3.37	ND	11	12	190
L85N 53+25W	.1	ND	15	14	21	34	2.97	ND	11	10	172
L85N 53+50W	.1	8	15	14	16	68	3.42	ND	9	9	201
L85N 53+75W	.1	8	20	9	20	73	2.22	ND	8	12	107
L85N 54+00W	.1	3	10	10	21	35	2.83	ND	11	9	120
L85N 54+25W	.1	ND	10	9	31	38	2.71	1	16	9	105
L85N 54+50W	.1	3	15	13	28	75	3.04	1	18	10	74
L85N 54+75W	.1	ND	10	10	31	117	2.25	4	16	10	58
L85N 55+00W	.1	ND	10	10	36	48	2.48	1	18	11	109
L85N 55+25W	.1	4	5	9	25	32	2.39	ND	23	11	82
L85N 55+50W	.1	ND	5	14	30	51	3.56	ND	20	11	122
L85N 55+75W	.2	5	5	18	32	70	4.23	ND	26	10	77
L85N 56+00W	.3	ND	5	18	43	125	3.45	ND	30	12	110
L85N 56+25W	.6	ND	5	26	37	155	4.63	ND	41	10	108
L85N 56+50W	.1	ND	10	39	70	204	7.35	ND	51	6	180
L85N 56+75W	.1	ND	20	42	202	51	8.34	ND	77	6	110
L85N 57+00W	.1	ND	10	15	45	42	3.80	ND	24	12	146
L85N 57+25W	.1	3	10	13	42	23	3.76	ND	19	15	72
L85N 50+00W	.1	ND	5	13	36	30	2.89	ND	23	12	272
L85N 50+25W	.1	3	15	15	38	94	3.76	1	29	13	142
L85N 50+50W	.1	ND	15	13	35	77	3.38	ND	30	13	116
L85N 50+75W	.1	ND	15	12	31	51	3.87	ND	23	9	131
L85N 51+00W	.1	3	10	16	24	82	4.05	ND	17	13	167
L85N 51+25W	.1	6	15	8	31	16	2.50	ND	13	13	107
L85N 51+50W	.1	ND	10	16	40	88	3.79	ND	32	11	101
L85N 51+75W	.2	11	30	21	18	115	5.35	ND	14	13	244
L85N 52+00W	.3	15	20	16	7	74	4.56	1	4	8	104
L85N 52+25W	.1	7	10	14	22	56	4.35	ND	12	11	102
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU #PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PR PPM	ZN PPM
L95N 65+00W	.1	3	5	13	21	54	3.74	1	10	16	193
L95N 65+25W	.3	8	ND	14	22	135	3.15	2	13	17	125
L95N 65+50W	.9	ND	5	16	29	283	3.78	4	28	18	203
L95N 65+75W	.3	ND	5	13	20	123	3.11	2	17	21	96
L97N 50+00W	.1	6	15	10	23	67	2.75	1	15	21	86
L97N 50+25W	.1	ND	10	9	31	41	3.18	ND	27	13	88
L97N 50+50W	.1	7	5	6	21	33	2.56	2	8	17	62
L97N 50+75W	.1	5	5	5	18	95	2.06	3	8	14	44
L97N 51+00W	.1	ND	35	11	32	222	3.27	ND	22	15	55
L97N 51+25W	.1	ND	10	7	26	43	3.11	1	12	12	71
L97N 51+50W	.1	6	10	6	21	42	2.39	1	10	17	62
L97N 51+75W	.1	4	15	9	19	86	2.75	2	10	20	85
L97N 52+00W	.1	ND	25	10	26	106	2.89	1	15	11	56
L97N 52+25W	.1	9	5	6	17	26	2.19	1	7	15	51
L97N 52+50W	.1	ND	45	13	29	342	4.28	1	18	8	63
L97N 52+75W	.1	ND	50	12	34	467	3.67	ND	25	7	66
L97N 53+00W	.1	ND	20	8	25	123	2.92	1	16	14	74
L97N 53+25W	.1	ND	70	9	28	263	3.72	2	19	7	101
L97N 53+50W	.1	ND	30	8	30	273	3.42	1	19	5	81
L97N 53+75W	.1	ND	40	9	31	275	3.64	ND	22	4	76
L97N 54+00W	.1	ND	35	7	25	211	2.94	1	23	12	82
L97N 54+25W	.1	ND	10	8	30	241	3.34	1	21	9	44
L97N 54+50W	.1	ND	10	12	32	123	3.28	ND	28	8	86
L97N 54+75W	.1	ND	10	8	41	254	3.89	1	24	10	98
L97N 55+00W	.1	ND	60	12	31	215	4.47	1	24	12	100
L97N 55+25W	.1	ND	10	11	40	171	2.97	1	30	10	76
L97N 55+50W	.1	ND	50	11	36	2506	4.03	1	24	8	69
L97N 55+75W	.1	ND	190	13	17	474	5.64	ND	11	13	76
L97N 56+00W	.1	ND	240	12	41	2725	4.43	1	21	11	49
L97N 56+25W	1.2	ND	40	19	34	946	3.31	1	65	25	61
L97N 56+50W	.8	ND	25	13	39	736	3.78	1	34	22	76
L97N 56+75W	.6	ND	15	11	32	373	2.85	2	25	21	72
L97N 57+00W	.2	ND	30	13	29	1148	3.39	2	21	20	64
L97N 57+25W	.2	3	40	12	27	1442	3.00	2	18	19	59
L97N 57+50W	.8	12	30	6	14	150	2.27	4	6	24	36
L97N 57+75W	.4	3	20	20	24	584	4.83	3	18	27	126
L97N 58+00W	.3	ND	30	18	26	346	4.48	4	18	27	134
L97N 58+25W	.1	4	45	23	20	975	3.61	12	14	19	78
L97N 58+50W	.1	ND	40	17	19	362	4.78	5	14	16	78
DETECTION LIMIT	.1	3	#5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L85N 52+50W	.1	15	20	15	19	163	3.75	2	14	13	47
L85N 52+75W	.2	8	5	10	34	19	2.44	1	22	11	102
L85N 53+00W	.1	10	5	7	21	19	2.48	1	7	11	53
L85N 53+25W	.5	6	5	16	11	187	3.78	1	10	15	96
L85N 53+50W	.4	ND	5	17	13	122	4.21	ND	11	9	114
L85N 53+75W	.1	ND	5	13	21	52	3.54	ND	15	8	129
L85N 54+00W	.1	ND	10	15	27	202	3.97	1	22	10	114
L85N 54+25W	.1	ND	5	15	30	52	3.76	ND	25	10	202
L85N 54+50W	.1	ND	5	11	24	74	3.01	1	16	12	119
L85N 54+75W	.2	5	25	13	18	58	3.62	1	11	16	179
L85N 55+00W	.1	8	20	10	17	55	3.21	1	9	11	121
L85N 55+25W	.1	5	20	9	15	70	2.98	1	7	10	101
L85N 55+50W	.2	ND	20	12	25	68	3.57	1	11	13	238
L85N 55+75W	.2	4	10	13	21	67	3.34	ND	11	10	271
L85N 56+00W	.2	4	45	11	23	124	3.18	1	10	10	114
L85N 56+25W	.1	ND	15	17	28	202	4.60	1	16	10	248
L85N 56+50W	.1	4	40	15	24	216	3.90	2	14	11	85
L85N 56+75W	.1	5	10	7	22	22	2.73	1	9	11	87
L85N 57+00W	.1	7	15	11	31	44	2.99	1	17	7	73
L85N 57+25W	.1	3	25	11	31	22	2.88	1	18	12	123
L85N 57+50W	.1	6	5	11	30	45	2.74	1	22	10	135
L85N 57+75W	.1	6	5	10	23	28	2.83	1	12	13	99
L85N 58+00W	.1	4	5	10	26	27	3.02	ND	16	9	90
L85N 58+25W	.1	4	10	7	20	16	2.27	1	11	9	84
L85N 58+50W	.1	8	5	7	22	27	1.89	1	11	8	54
L85N 58+75W	.1	7	10	9	24	31	2.86	1	13	8	98
L85N 59+00W	.1	3	5	9	29	22	2.54	ND	17	10	87
L85N 59+25W	.1	8	5	9	23	19	2.75	1	12	11	87
L85N 59+50W	.1	6	5	9	25	33	2.53	1	14	11	79
L85N 59+75W	.1	ND	5	12	34	33	3.29	1	17	11	114
L85N 60+00W	.1	4	10	13	39	26	3.25	1	21	8	44
L87N 50+25W	.1	9	15	14	21	117	3.24	3	12	16	362
L87N 50+50W	.1	5	20	15	28	225	3.57	1	19	11	109
L87N 50+75W	.1	ND	25	16	29	112	3.60	1	24	9	113
L87N 51+00W	.1	ND	15	21	31	370	4.27	1	23	7	97
L87N 51+25W	.1	ND	55	16	25	384	4.02	1	17	6	89
L87N 51+50W	.1	7	35	16	23	317	3.68	2	16	10	81
L87N 51+75W	.1	7	25	12	24	163	2.67	2	15	10	90
L87N 52+00W	.1	8	35	17	27	303	4.87	3	19	61	131
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L87N 52+25W	.1	10	40	15	24	301	3.91	3	19	17	92
L87N 52+50W	.1	7	15	11	26	130	2.70	1	18	12	66
L87N 52+75W	.3	8	25	11	25	139	2.77	1	18	14	61
L87N 53+00W	.2	8	5	10	30	94	2.36	1	23	12	62
L87N 53+25W	.4	4	5	11	29	101	2.52	1	21	15	100
L87N 53+50W	.3	11	20	11	28	143	3.06	2	17	14	62
L87N 53+75W	.5	6	10	11	25	136	2.84	1	16	17	77
L87N 54+00W	.2	11	25	12	23	136	3.46	2	15	17	74
L87N 54+25W	.1	3	10	10	29	95	2.43	1	23	13	67
L87N 54+50W	.3	7	10	11	32	74	2.28	1	24	13	50
L87N 54+75W	.3	7	10	10	23	60	2.12	1	12	15	91
L87N 55+00W	.4	3	10	12	22	136	2.89	1	15	14	111
L87N 55+25W	.3	7	15	12	22	102	3.09	1	14	13	63
L87N 55+50W	.2	14	30	14	19	128	3.39	3	10	12	62
L87N 55+75W	.3	15	30	14	19	129	3.48	2	11	13	61
L87N 56+00W	.1	8	10	15	19	93	3.43	2	9	16	122
L87N 56+75W	.2	8	10	12	29	59	3.31	1	19	13	156
L87N 57+00W	.2	6	5	12	25	96	2.88	1	17	13	63
L87N 57+25W	.1	5	5	9	32	26	2.67	1	15	11	151
L87N 57+50W	.1	3	10	8	25	31	2.27	1	13	10	201
L87N 57+75W	.1	ND	10	10	28	39	3.02	ND	32	7	107
L87N 58+00W	.1	3	20	10	27	37	2.93	ND	20	7	107
L87N 58+25W	.1	ND	25	18	41	117	4.04	ND	38	5	89
L87N 58+50W	.1	ND	10	9	25	30	2.58	ND	14	8	90
L87N 58+75W	.1	ND	10	10	25	30	2.71	ND	12	7	100
L87N 59+25W	.1	ND	20	19	41	115	4.28	ND	37	6	97
L87N 59+50W	.1	3	25	19	37	111	4.15	ND	38	5	88
L87N 59+75W	.1	ND	15	15	36	68	3.54	ND	28	7	106
L87N 60+00W	.1	ND	15	14	33	61	3.27	ND	25	9	104
L87N 60+25W	.1	ND	5	14	32	58	3.24	1	24	16	100
L87N 60+50W	.1	ND	10	13	33	61	3.32	ND	27	10	93
L89N 50+25W	.1	ND	20	19	30	609	4.15	6	18	9	117
L89N 50+50W	.1	ND	25	21	32	548	4.59	5	18	11	116
L89N 50+75W	.1	6	35	15	22	157	3.68	2	10	12	174
L89N 51+00W	.1	4	10	13	24	105	4.07	1	13	15	145
L89N 51+25W	.1	ND	20	11	29	74	3.84	1	20	13	193
L89N 51+50W	.1	5	15	9	21	38	2.90	1	8	12	74
L89N 51+75W	.1	3	5	9	15	36	2.85	ND	7	12	62
L89N 52+00W	.1	3	25	12	24	78	3.56	1	16	11	130
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE Z	MO PPM	NI PPM	PB PPM	ZN PPM
L89N 52+25W	.1	ND	5	13	20	56	3.17	1	13	12	173
L89N 52+50W	.1	ND	20	7	18	22	2.53	1	9	13	75
L89N 52+75W	.1	ND	15	10	23	31	3.13	ND	20	10	145
L89N 53+00W	.1	ND	35	7	19	23	2.59	1	12	11	94
L89N 53+25W	.1	ND	15	8	22	26	2.68	1	12	12	103
L89N 53+50W	.1	ND	10	10	22	88	2.82	ND	16	10	132
L89N 53+75W	.1	ND	15	13	27	138	3.67	1	20	11	112
L89N 54+00W	.1	ND	25	15	27	188	4.03	1	23	9	124
L89N 54+25W	.1	ND	25	17	27	164	3.83	ND	23	8	222
L89N 54+50W	.1	3	30	15	29	200	3.94	1	18	11	104
L89N 54+75W	.1	ND	15	13	28	166	3.61	1	23	6	134
L89N 55+00W	.1	ND	25	13	25	180	3.64	1	17	6	155
L89N 55+25W	.1	3	30	13	25	149	3.67	1	14	6	141
L89N 55+50W	.1	7	20	14	26	153	3.62	1	14	9	63
L89N 55+75W	.1	3	15	12	28	96	3.36	1	15	8	108
L89N 56+00W	.1	3	15	9	22	46	2.57	1	12	9	153
L89N 56+25W	.1	7	15	11	22	133	3.60	1	11	13	58
L89N 56+50W	.2	8	10	12	23	103	3.07	1	14	10	79
L89N 56+75W	.1	10	10	12	23	93	3.02	1	14	12	62
L89N 57+00W	.1	ND	10	13	25	87	3.07	1	16	8	94
L89N 57+25W	.1	3	20	11	26	85	2.58	1	29	10	75
L89N 57+50W	.1	6	15	13	22	89	3.11	1	17	9	67
L89N 57+75W	.1	12	20	12	21	104	3.43	1	15	9	63
L89N 58+00W	.1	6	60	21	31	629	4.80	3	23	11	108
L89N 58+50W	.1	4	15	10	17	64	2.66	ND	8	9	110
L89N 58+75W	.1	7	10	14	26	224	3.91	1	15	9	68
L89N 59+00W	.1	ND	15	14	25	99	3.55	1	15	8	149
L89N 59+25W	.1	ND	10	17	29	205	3.71	1	21	7	124
L89N 59+50W	.1	ND	10	16	29	245	3.12	1	21	9	112
L89N 59+75W	.1	5	25	10	21	64	2.70	1	13	12	72
L89N 60+00W	.1	5	10	12	26	139	2.92	1	19	9	89
L89N 61+00W	.7	ND	5	29	74	1034	7.74	3	69	4	281
L91N 50+25W	.1	4	10	7	25	104	3.00	3	11	13	81
L91N 50+50W	.1	4	10	5	22	78	2.61	4	9	11	68
L91N 50+75W	.1	5	10	7	24	88	2.85	4	10	9	74
L91N 51+00W	.1	3	10	9	26	62	2.89	1	13	10	84
L91N 51+25W	.3	7	10	10	25	222	2.82	2	12	12	95
L91N 51+50W	.4	6	10	9	24	1841	2.71	2	11	12	101
L91N 51+75W	.4	7	30	15	27	271	3.77	3	16	14	76
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU #PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L91N 52+00W	.1	4	35	14	26	228	3.60	1	15	16	69
L91N 52+25W	.1	3	25	9	24	106	3.54	1	12	13	98
L91N 52+50W	.1	ND	15	10	26	308	3.76	1	14	14	123
L91N 52+75W	.1	3	15	10	22	166	3.55	1	12	14	109
L91N 53+00W	.1	8	20	7	19	59	2.99	1	8	18	104
L91N 53+25W	.1	3	20	8	20	80	3.33	1	8	17	107
L91N 53+50W	.1	ND	20	9	30	88	3.77	ND	15	11	91
L91N 53+75W	.1	ND	20	9	22	101	3.12	ND	11	13	148
L91N 54+00W	.1	3	20	8	24	87	3.39	ND	11	18	78
L91N 54+25W	.1	ND	20	12	32	171	4.27	ND	21	11	125
L91N 54+50W	.1	ND	20	8	23	99	3.59	ND	11	15	119
L91N 54+75W	.1	ND	20	12	25	84	3.85	ND	17	10	161
L91N 55+00W	.1	ND	10	11	24	223	3.24	ND	13	9	86
L91N 55+25W	.1	ND	10	13	30	188	4.03	ND	28	11	107
L91N 55+50W	.1	8	10	10	26	84	2.89	1	14	18	92
L91N 55+75W	.1	ND	10	14	28	266	3.78	ND	25	12	148
L91N 56+25W	.1	ND	20	14	31	227	3.44	2	23	15	142
L91N 56+50W	.1	ND	20	16	28	175	3.32	ND	19	14	228
L91N 56+75W	.1	8	10	9	22	85	2.97	ND	10	14	126
L91N 57+00W	.1	5	10	9	21	80	3.49	ND	11	15	107
L91N 57+25W	.1	10	20	11	22	78	3.15	ND	26	17	95
L91N 57+50W	.1	6	15	10	22	94	3.20	ND	17	15	118
L91N 57+75W	.3	4	25	12	24	80	3.30	ND	17	18	112
L91N 58+00W	.1	6	5	14	25	135	3.21	ND	16	16	75
L91N 58+25W	.1	4	10	13	23	109	3.23	ND	14	15	94
L91N 58+50W	.1	ND	30	17	31	211	4.07	ND	24	14	98
L91N 58+75W	.1	3	20	17	25	277	3.85	1	12	12	94
L91N 59+00W	.1	5	20	12	21	93	2.76	ND	12	14	138
L91N 59+25W	.1	ND	10	14	26	85	3.43	ND	18	8	113
L91N 59+50W	.1	ND	10	12	22	81	3.17	ND	12	10	139
L91N 59+75W	.1	5	30	14	23	162	4.04	ND	11	10	70
L91N 60+00W	.1	7	35	15	24	229	3.76	1	12	11	77
L91N 60+25W	.1	6	10	14	21	95	3.40	ND	12	9	104
L91N 60+50W	.1	6	10	13	20	86	3.26	ND	11	9	101
L91N 60+75W	.1	7	20	13	22	88	3.39	ND	13	11	111
L91N 61+00W	.1	ND	35	14	20	77	3.27	ND	13	8	242
L91N 61+25W	.1	3	10	14	20	81	3.36	ND	14	8	243
L91N 61+50W	.1	7	15	10	20	74	2.86	ND	11	13	137
L91N 61+75W	.1	6	10	10	23	64	3.13	ND	10	11	112
DETECTION LIMIT	.1	3	#5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MG PPM	NI PPM	PB PPM	ZN PPM
L93N 50+25W	.1	5	20	8	37	510	2.66	2	19	6	145
L93N 50+50W	.1	4	10	14	48	2479	2.91	3	29	8	218
L93N 50+75W	.1	6	10	14	47	1180	2.67	3	26	7	125
L93N 51+00W	.1	ND	10	14	51	87	3.70	1	30	8	176
L93N 51+25W	.1	ND	20	19	39	219	3.99	1	27	10	61
L93N 51+50W	.1	9	10	7	33	38	2.37	1	12	6	61
L93N 51+75W	.1	6	30	9	35	106	3.16	2	19	6	45
L93N 52+00W	.1	14	10	5	23	30	2.04	1	7	10	41
L93N 52+25W	.1	16	20	5	18	38	2.01	1	6	8	30
L93N 52+50W	.1	10	20	9	23	108	3.17	1	12	11	61
L93N 52+75W	.2	9	25	9	22	709	3.07	2	11	8	75
L93N 53+00W	.1	12	30	13	24	530	3.59	2	12	9	67
L93N 53+25W	.1	4	40	17	28	1003	3.94	3	19	7	90
L93N 53+50W	.1	ND	55	21	33	909	4.59	2	19	10	84
L93N 53+75W	.1	6	20	19	31	302	4.40	2	19	8	76
L93N 54+00W	.1	7	15	28	24	493	5.16	2	18	21	175
L93N 54+25W	.1	ND	15	15	38	396	4.58	ND	22	13	71
L93N 54+50W	.1	ND	140	25	15	1392	7.41	ND	14	8	106
L93N 54+75W	.6	ND	500	22	15	966	10.87	ND	12	6	142
L93N 55+00W	.1	ND	65	20	26	1036	5.80	ND	19	10	75
L93N 55+25W	.5	ND	40	14	29	229	4.58	1	26	16	165
L93N 55+50W	.4	ND	5	14	29	297	4.61	1	20	18	139
L93N 55+75W	.5	5	10	9	24	62	3.33	1	11	15	121
L93N 56+00W	.4	3	5	10	29	55	3.45	1	16	14	243
L93N 56+25W	.4	9	5	9	26	37	3.04	1	9	12	107
L93N 56+50W	.4	10	35	13	27	107	3.75	1	14	11	76
L93N 56+75W	.5	8	15	13	28	214	3.76	1	16	17	97
L93N 57+00W	.3	5	15	14	26	128	4.05	ND	16	13	97
L93N 57+25W	.5	13	25	15	28	137	4.14	1	12	14	62
L93N 57+50W	.6	11	35	16	28	154	4.40	1	15	13	62
L93N 57+75W	.6	6	20	14	25	153	3.96	1	12	14	74
L93N 58+00W	.8	ND	20	13	25	158	3.96	ND	16	13	137
L93N 58+25W	.5	ND	40	19	22	222	4.98	ND	19	28	201
L93N 58+50W	.1	ND	10	19	26	162	4.58	ND	23	22	291
L93N 58+75W	.1	ND	40	17	29	224	4.58	ND	19	14	125
L93N 59+00W	.2	ND	10	17	27	123	4.24	ND	18	14	161
L93N 59+25W	.2	ND	20	19	30	168	4.75	ND	26	16	174
L93N 59+50W	.1	ND	5	20	31	163	4.58	ND	27	17	179
L93N 59+75W	.3	ND	10	23	10	184	5.16	ND	14	10	105
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE %	MO PPM	NI PPM	PB PPM	ZN PPM
L93N 60+00W	.1	ND	35	14	21	215	3.62	ND	19	17	133
L93N 60+25W	.1	ND	35	15	27	267	4.08	1	20	14	125
L93N 60+50W	.1	ND	10	20	13	83	3.79	ND	13	28	158
L93N 60+75W	.1	ND	5	21	26	243	4.54	ND	25	37	289
L93N 61+00W	.1	ND	5	19	26	180	4.29	ND	23	16	251
L93N 61+25W	.1	ND	20	15	24	190	3.90	ND	19	14	114
L93N 61+50W	.1	ND	45	15	26	390	4.32	1	18	13	99
L93N 61+75W	.1	ND	5	12	22	106	3.89	2	11	10	231
L93N 62+00W	.1	ND	20	12	22	112	3.90	1	11	10	242
L93N 62+25W	.1	8	25	13	23	81	3.42	1	12	9	78
L93N 62+50W	.1	12	10	12	22	140	3.44	1	16	7	87
L93N 62+75W	.1	12	20	11	21	121	3.17	1	13	9	74
L93N 63+00W	.1	4	15	16	26	184	3.79	1	20	9	84
L93N 63+25W	.1	8	5	14	20	87	3.37	2	13	12	146
L93N 63+50W	.1	ND	15	13	27	195	3.44	1	21	10	116
L93N 63+75W	.1	7	5	12	25	68	3.04	1	16	10	78
L93N 64+00W	.1	8	5	10	25	49	3.02	1	14	9	108
L93N 64+25W	.1	8	5	12	30	111	3.16	1	20	9	122
L93N 64+50W	.1	7	5	12	27	95	3.20	1	20	11	128
L94N 51+00W	.1	11	5	8	35	38	2.41	1	23	10	109
L95N 50+25W	.1	14	5	4	55	16	1.82	1	31	7	32
L95N 50+50W	.1	8	30	7	27	93	2.62	ND	19	8	44
L95N 50+75W	.1	4	10	7	29	122	3.08	1	15	5	67
L95N 51+25W	.1	ND	15	8	34	48	3.97	1	18	11	199
L95N 51+50W	.1	ND	15	9	31	158	3.75	ND	19	8	166
L95N 51+75W	.1	ND	15	10	33	122	4.05	ND	22	10	116
L95N 52+00W	.1	3	20	9	28	76	3.27	1	14	6	83
L95N 52+25W	.1	ND	40	11	32	156	3.30	1	20	11	99
L95N 52+50W	.1	ND	30	9	33	101	3.75	1	20	11	74
L95N 52+75W	.1	ND	30	11	36	226	3.80	1	25	12	95
L95N 53+00W	.1	ND	30	12	34	242	4.09	1	27	10	93
L95N 53+25W	.1	8	40	11	26	319	3.52	1	18	8	61
L95N 53+50W	.1	ND	20	11	33	203	4.94	1	23	6	109
L95N 53+75W	.1	ND	130	11	29	624	4.69	1	19	5	72
L95N 54+00W	.1	ND	10	17	55	156	5.22	ND	41	8	168
L95N 54+25W	.1	ND	10	16	38	206	4.70	1	32	7	138
L95N 54+50W	.1	ND	40	12	31	257	4.58	ND	21	6	143
L95N 54+75W	.1	11	50	9	22	376	4.15	2	9	7	47
L95N 55+00W	.1	5	25	14	29	138	3.65	1	18	7	55
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

SAMPLE NAME	AG PPM	AS PPM	AU *PPB	CO PPM	CR PPM	CU PPM	FE I	MG PPM	NI PPM	PB PPM	ZN PPM
L95N 55+25W	.1	13	70	7	18	107	2.75	3	9	5	38
L95N 55+50W	.1	5	25	9	19	143	3.07	2	14	8	83
L95N 55+75W	.1	12	80	4	15	37	2.34	1	3	8	43
L95N 56+00W	.1	13	20	5	17	82	2.58	1	6	11	68
L95N 56+25W	.1	5	20	11	22	562	2.54	1	11	5	46
L95N 56+50W	.1	13	30	5	17	145	2.40	2	5	5	42
L95N 56+75W	.1	6	20	12	19	169	3.72	ND	8	6	161
L95N 57+00W	.1	4	20	10	18	81	3.40	ND	9	9	164
L95N 57+25W	.1	8	25	10	19	75	3.16	2	10	12	116
L95N 57+50W	.1	ND	25	11	15	319	5.30	15	15	29	206
L95N 57+75W	.1	5	5	9	16	152	3.57	4	8	10	129
L95N 58+00W	.1	9	5	9	18	83	2.90	2	8	12	91
L95N 58+25W	.1	ND	10	7	21	58	3.16	1	9	9	161
L95N 58+50W	.1	ND	10	10	21	88	3.34	1	9	12	138
L95N 58+75W	.1	ND	10	10	21	91	3.33	ND	10	7	151
L95N 59+00W	.1	ND	40	12	26	271	4.35	2	19	9	131
L95N 59+25W	.1	ND	40	11	24	202	3.60	1	15	11	100
L95N 59+50W	.1	ND	30	11	23	149	3.40	ND	15	9	126
L95N 59+75W	.1	ND	30	13	26	290	4.07	ND	19	8	107
L95N 60+00W	.1	ND	10	13	24	151	3.45	ND	27	14	228
L95N 60+25W	.1	ND	50	11	24	999	3.54	ND	34	21	104
L95N 60+50W	.1	ND	30	11	21	393	3.35	ND	22	18	171
L95N 60+75W	.1	3	40	14	21	244	3.55	ND	19	14	163
L95N 61+00W	.1	ND	35	12	20	383	3.72	ND	14	16	149
L95N 61+25W	.5	6	45	9	14	53	2.47	ND	6	31	248
L95N 61+50W	.1	ND	30	13	21	209	3.37	1	13	37	227
L95N 61+75W	.1	4	15	10	18	69	2.79	1	12	11	140
L95N 62+00W	.1	9	5	11	19	68	2.95	1	10	11	134
L95N 62+25W	.1	8	5	10	21	49	2.62	1	11	14	219
L95N 62+50W	.1	6	20	13	21	177	3.54	2	12	11	101
L95N 62+75W	.1	ND	10	17	18	272	3.22	1	13	22	210
L95N 63+00W	.1	ND	20	15	23	304	3.60	1	15	19	159
L95N 63+25W	.1	11	20	16	21	233	3.82	2	14	19	107
L95N 63+50W	.1	ND	20	14	21	234	3.55	2	11	14	276
L95N 63+75W	.1	6	25	12	16	227	4.22	1	10	20	141
L95N 64+00W	.1	ND	25	22	28	2057	4.44	5	23	19	273
L95N 64+25W	.1	6	5	13	21	115	3.27	1	10	14	240
L95N 64+50W	.1	6	15	10	23	130	2.92	2	12	7	90
L95N 64+75W	.4	ND	10	19	26	427	4.04	5	24	14	161
DETECTION LIMIT	.1	3	*5	1	1	1	.01	1	1	2	1

E & B EXPLORATIONS INC.
 CARIBOO BELL PROJECT
 I.P. PSEUDOSECTION

INDUCED POLARIZATION AND RESISTIVITY SURVEY


POLE - DIPOLE ARRAY PSEUDOSECTION

GEOLOGICAL BRANCH
 ASSESSMENT REPORT

16,040

PART
 3 OF 3


LEGEND
 PSEUDOSECTION CONTOURS (Intervals as indicated)
 Ma GREATER THAN 40 ms.
 Ma 25.1 ms. TO 40 ms.
 Ma 12.5 ms. TO 25 ms.



SCALE: 1:1250

LINE NO. 9300 N

LINE NO. 9300 N



E & B EXPLORATIONS INC.
 CARIBOO BELL PROJECT
 I.P. PSEUDOSECTION

INDUCED POLARIZATION AND RESISTIVITY SURVEY

POLE-DIPOLE ARRAY PSEUDOSECTION



16,040

PART
 3 OF 3


LEGEND
 PSEUDOSECTION CONTOURS (Intervals as indicated)
 Ma GREATER THAN 40 ms.
 Ma 25.1 ms. TO 40 ms.
 Ma 12.5 ms. TO 25 ms.

SCALE: 1:1250

LINE NO. 9500 N

LINE NO. 9500 N

IR INTERPRETEX
 RESOURCES LTD.
 N.T.S. DRAWN BY




E & B EXPLORATIONS INC.
CARIBOO BELL PROJECT
I.P. PSEUDOSECTION

INDUCED POLARIZATION AND RESISTIVITY SURVEY

POLE - DIPOLE ARRAY PSEUDOSECTION

16,040 PART 3 OF 3

LEGEND
PSEUDOSECTION CONTOURS (Intervals as Indicated)
Ma GREATER THAN 40 mS.
Ma 25.1 mS. TO 40 mS.
Ma 12.5 mS. TO 25 mS.




IR INTERPRETEX RESOURCES LTD. SCALE 1:1250 DATE OCT/86 PROJECT 86616 FIGURE NO. NTS DRAWN BY

SCALE: 1:1250

LINE NO. 9700 N

LINE NO. 9700 N



E & B EXPLORATIONS INC.
 CARIBOO BELL PROJECT
 I.P. PSEUDOSECTION


INDUCED POLARIZATION AND RESISTIVITY SURVEY
 POLE - DIPOLE ARRAY PSEUDOSECTION

GEOLOGICAL BRANCH
 ASSESSMENT REPORT

PART
 3 OF 3

16,040

LEGEND
 PSEUDOSECTION CONTOURS (Intervals as Indicated)
 Ma GREATER THAN 40 ms.
 Ma 25.1 ms. TO 40 ms.
 Ma 12.5 ms. TO 25 ms.




SCALE 1:1250

LINE NO. 9800 N

LINE NO. 9800 N

TO ACCOMPANY REPORT BY E.R. ROCKEL
 IR INTERPRETEX RESOURCES LTD.

SCALE 1:1250	DATE OCT. 7 '86
PROJECT 88616	FIGURE NO.
NTS	DRAWN BY




E & B EXPLORATIONS INC.
 CARIBOO BELL PROJECT
 I.P. PSEUDOSECTION
 TO ACCOMPANY REPORT BY E.R. ROCKEL
 IR INTERPRETEX RESOURCES LTD.
 SCALE: 1:1250 DATE: OCT/86
 PROJECT: 86616 FIGURE NO.:
 INTS DRAWN BY:

INDUCED POLARIZATION AND RESISTIVITY SURVEY

LEGEND
 PSEUDOSECTION CONTOURS (Intervals as Indicated)
 Ma GREATER THAN 40 mS.
 Ma 25.1 mS. TO 40 mS.
 Ma 12.5 mS. TO 25 mS.

POLE-DIPOLE ARRAY PSEUDOSECTION




GEOLOGICAL BRANCH
 ASSESSMENT REPORT

16,040

PART
 3 OF 3

LINE NO. 10600 N

LINE NO. 10600 N



E & B EXPLORATIONS INC.
 CARIBOO BELL PROJECT
 I.P. PSEUDOSECTION


TO ACCOMPANY REPORT BY E.R. ROCKEL

IR INTERPRETEX RESOURCES LTD.
 SCALE 1:1250 DATE OCT./86
 PROJECT B6616 FIGURE NO. NTS DRAWN BY

INDUCED POLARIZATION AND RESISTIVITY SURVEY

LEGEND
 PSEUDOSECTION CONTOURS (Intervals as indicated)
 Ma GREATER THAN 40 mS.
 Ma 25.1 mS. TO 40 mS.
 Ma 12.5 mS. TO 25 mS.

SCALE: 1:1250




GEOLOGICAL BRANCH
 ASSESSMENT REPORT

16,040

PART
 3 OF 3

LINE NO. 10800 N

LINE NO. 10800 N




E & B EXPLORATIONS INC.
 CARIBOO BELL PROJECT
 I.P. PSEUDOSECTION

TO ACCOMPANY REPORT BY E.R. ROCKEL
 INTERPRETEX
 RESOURCES LTD.

INDUCED POLARIZATION AND RESISTIVITY SURVEY
LEGEND
 PSEUDOSECTION CONTOURS (Intervals as indicated)
 Ma GREATER THAN 40 mS.
 Ma 25.1 mS. TO 40 mS.
 Ma 12.5 mS. TO 25 mS.

SCALE 1:1250




LINE NO. 11200 N

GEOLOGICAL BRANCH
 ASSESSMENT REPORT

16,040

PART
 3 OF 3

LINE NO. 11200 N



E & B EXPLORATIONS INC.
 CARIBOO BELL PROJECT
 I.P. PSEUDOSECTION
 TO ACCOMPANY REPORT BY E.R. ROCKEL
 INTERPRETEX RESOURCES LTD.
 SCALE: 1:1250 DATE: OCT. / 86
 PROJECT: 86616 FIGURE NO.:
 NT3 DRAWN BY:

INDUCED POLARIZATION AND RESISTIVITY SURVEY

POLE-DIPOLE ARRAY PSEUDOSECTION

GEOLOGICAL BRANCH
 ASSESSMENT REPORT



PART
 3 OF 3

16,040

LINE NO. 11300 N


LINE NO. 11300 N

LEGEND
 PSEUDOSECTION CONTOURS (Intervals as indicated)
 Ma GREATER THAN 40 mS.
 Ma 25.1 mS. TO 40 mS.
 Ma 12.5 mS. TO 25 mS.
 SCALE: 1:1250



E & B EXPLORATIONS INC.
 CARIBOO BELL PROJECT
 I.P. PSEUDOSECTION
 TO ACCOMPANY REPORT BY E.R. ROCKEL
 IR INTERPRETEX
 RESOURCES LTD. NTS


INDUCED POLARIZATION AND RESISTIVITY SURVEY
LEGEND
 PSEUDOSECTION CONTOURS (Intervals as Indicated)
 Ma GREATER THAN 40 ms.
 Ma 25.1 ms. TO 40 ms.
 Ma 12.5 ms. TO 25 ms.
 SCALE: 1:1250



POLE-DIPOLE ARRAY PSEUDOSECTION
16,040
 LINE NO. 11400 N

PART
 3 OF 3

LINE NO. 11400 N




E & B EXPLORATIONS INC.
 CARIBOO BELL PROJECT
 I.P. PSEUDOSECTION
 TO ACCOMPANY REPORT BY E.R. ROCKEL
 IR INTERPRETEX RESOURCES LTD. SCALE 1:1250 DATE OCT. / 86 PROJECT 88616 FIGURE NO. INTS DRAWN BY

INDUCED POLARIZATION AND RESISTIVITY SURVEY

LEGEND
 PSEUDOSECTION CONTOURS (Intervals as Indicated)
 Ma GREATER THAN 40 ms.
 Ma 25.1 ms. TO 40 ms.
 Ma 12.5 ms. TO 25 ms.

POLE-DIPOLE ARRAY PSEUDOSECTION




GEOLOGICAL BRANCH ASSESSMENT REPORT

PART 3 of 3

16,040

LINE NO. 11500 N

LINE NO. 11500 N



E & B EXPLORATIONS INC.
 CARIBOO BELL PROJECT
 I.P. PSEUDOSECTION


INDUCED POLARIZATION AND RESISTIVITY SURVEY

POLE-DIPOLE ARRAY PSEUDOSECTION

GEOLOGICAL BRANCH
 ASSESSMENT REPORT

PART
 3 OF 3


LEGEND
 PSEUDOSECTION CONTOURS (Intervals as Indicated)
 Ma GREATER THAN 40 ms.
 Ma 25.1 ms. TO 40 ms.
 Ma 12.5 ms. TO 25 ms.



16,040

LINE NO. 11600 N

LINE NO. 11600 N




E & B EXPLORATIONS INC.
 CARIBOO BELL PROJECT
 I.P. PSEUDOSECTION

INDUCED POLARIZATION AND RESISTIVITY SURVEY

POLE-DIPOLE ARRAY PSEUDOSECTION

GEOLOGICAL BRANCH
 ASSESSMENT REPORT

LEGEND
 PSEUDOSECTION CONTOURS (Intervals as Indicated)
 Ma GREATER THAN 40 mS.
 Ma 25.1 mS. TO 40 mS.
 Ma 12.5 mS. TO 25 mS.



16,040 PART 3 OF 3

LINE NO. 11700 N

LINE NO. 11700 N

IR INTERPRETEX RESOURCES LTD.
 SCALE: 1:1250 DATE: OCT. 78
 PROJECT: 86616 FIGURE NO.:
 NT3 DRAWN BY:

