

FOX GEOLOGICAL CONSULTANTS LTD.

LOG NO: <i>April 30/91</i> RD.
ACTION:
FILE NO:

GEOCHEMICAL REPORT FOR THE FAWNIE PROSPECT

FAWN 1 TO 4 MINERAL CLAIMS

OMINECA MINING DIVISION

BRITISH COLUMBIA

NTS 93F/6

125°06'W 53°17'N

by

**Geoff N. Goodall, B.Sc.
Fox Geological Consultants Ltd.
1409 - 409 Granville Street
Vancouver, B.C. V6C 1T8**

**Owned and Operated by
Placer Dome Inc.
15th Floor - 1055 Dunsmuir Street
Vancouver, B.C. V7X 1P1**

Annual Work Approval #130040-4910

April 18, 1991

**GEOLOGICAL BRANCH
ASSESSMENT REPORT**

21,247

TABLE OF CONTENTS

	Page
SUMMARY	1
INTRODUCTION	2
LOCATION AND ACCESS	2
CLAIM INFORMATION	2
GEOLOGY	5
Regional	5
Local	7
PREVIOUS WORK	7
1990 WORK PROGRAM	7
RESULTS	8
CONCLUSIONS AND RECOMMENDATIONS	8
DISBURSEMENTS	9
CERTIFICATE	10

List of Tables

Table I - Claim Information	5
-----------------------------------	---

List of Figures

	Page
Figure 1 - Location Map	3
Figure 2 - Claim Map	4
Figure 3 - Regional Geology Map	6
Figure 4 - Gold Geochemical Results	pocket
Figure 5 - Arsenic Geochemical Results	pocket
Figure 6 - Zinc Geochemical Results	pocket
Figure 7 - Silver Geochemical Results	pocket

Appendices

APPENDIX I - Geochemical Analysis	11
---	----

SUMMARY

This report summarizes the results of the 1990 soil sampling program conducted on the Fawn 1 to 4 mineral claims situated southwest of Vanderhoof, B.C. in the Omineca Mining Division. The program included the extension of Grid A by six line-kilometres, establishing 11 line-kilometres in a separate area and collection of 375 soil samples and five rock samples. All samples were analyzed for 30 elements by ICP techniques and for gold by geochemical AA methods.

Results of the survey were encouraging. The geochemical samples returned moderate to highly anomalous values for silver, gold and zinc over portions of both grids. A high concentration of 133 ppm silver was obtained from Grid A and 5,196 ppm zinc from Grid B. Additionally five pits were dug by hand in the vicinity of highly anomalous samples collected previously from Grid A. Results of these pits confirmed the anomalous concentrations of silver, gold and zinc.

INTRODUCTION

This report provides information on a soil geochemical sampling program conducted on the Fawn 1 to 4 claims located in the Interior Plateau region of central B.C., 125 kilometres southwest of Vanderhoof. The prospect is 100% owned by Placer Dome Inc. and is at a preliminary grassroots exploration evaluation stage.



LOCATION AND ACCESS

The Fawn claims are situated on a ridge, four kilometres northeast of Fawnie Nose and 125 kilometres southwest of Vanderhoof, B.C. (Figure 1). The centre of the claim block is at 53°17'N, 125°06'E on NTS mapsheet 93F/6. The claims are accessed via helicopter from a staging point on the Kluskus Forest Service Road, 145 kilometres southwest of Vanderhoof. The Capoose mining road provides access for heavy machinery to within one kilometre of the Fawn claims.


Local terrain consists of subalpine to alpine meadows with rocky ridges occurring at higher elevations in the central and eastern portion of the claims.

CLAIM INFORMATION

The Fawnie prospect consists of four mineral claims totalling 72 units situated within the Omineca Mining Division on NTS mapsheet 93F/6. Claim data are given in Table I and a claim map in Figure 2. The Fawn 1 to 4 claims constitute the "A" group. Expiry dates assume that present work is accepted for assessment purposes.



PLACER DOME INC.			
PROPERTY LOCATION PLAN			
FAWN CLAIMS			
FOX GEOLOGICAL CONSULTANTS LTD.			
DATE		N.T.S.	Dwg. No.
			1



PLACER DOME INC			
PROJECT NO: 138		OMINECA M.D.	
CLAIM MAP FAWN 1 to 4 CLAIMS			
DATE	SCALE	NTS	FIG
20 / 11 / 89	1:50,000	93 F/6	2

Table I
Claim Information

Claim Name	Record No.	Units	Expiry Date
Fawn 1	10356	18	April 17, 1994
Fawn 2	10357	18	April 17, 1994
Fawn 3	10358	18	April 17, 1994
Fawn 4	10359	18	April 17, 1994


GEOLOGY

Regional


The Fawnie Range, mapped by H. W. Tipper for the G.S.C., is composed of moderately deformed, steeply dipping upper Triassic to lower Jurassic Takla Group in fault contact with a northwest trending sequence of synclinally folded lower to middle Jurassic Hazelton Group rocks (Figure 3). The granitic Capoose batholith of Cretaceous or Tertiary age intrudes both groups of rocks. Ootsa Lake Group rocks of Cretaceous or Tertiary age blanket the eastern portion of the region.

In the Fawnie area, Takla Group rocks consist of andesitic and basaltic flows, tuffs and breccias with interbedded argillite and minor limestone. Hazelton Group rocks are characterized by andesite and related tuffs and breccias, chert pebble conglomerate, shale and sandstone. Ootsa Lake Group consists of a series of volcanic flows, tuffs and breccias ranging in composition from basalt to rhyolite.

Low grade regional metamorphism is evident throughout the Triassic and Jurassic age rocks with a pronounced contact metamorphic effect around plutons. The Takla Group is moderately deformed with dips reaching 70°. Hazelton Group is characterized by open folds with dips up to 45°. In the vicinity of the Capoose prospect, rocks are synclinally folded with the axis trending northwest.



- | | | |
|----------|----|--|
| TERTIARY | 11 | Endako Group |
| | 10 | OOTSALAKE GROUP
Rhyolite, Dacite |
| | 9 | Basalt, Andesite |
| CRET. | 8 | Granite, Qtz Diorite
Granodiorite, Diorite |
| JURASSIC | 6 | HAZELTON GROUP
Greywacke, Argillite
Conglomerate |
| | 5 | Andesite, Chert pebble
Conglomerate |
| | 2 | TAKLA GROUP
Andesite and Basalt |
| TRIASSIC | | |
- GEOLOGIC CONTACT
 - - - FAULT



GEOLOGY AFTER H.W. TIPPER 1949 - 53

PLACER DOME INC.			
PROJECT NO 138	OMINECA M.D.		
FAWN CLAIMS REGIONAL GEOLOGY			
DATE	SCALE	NTS	FIG.
	1" = 4 mi.	93F6	3

Glacial direction in the region is dominantly northeast, creating several cirques on Fawnie Nose and northeast trending ridges and moraines on the Fawn claims.

Local

Rock exposure on the Fawn claims is limited to ridges and hills. Basalt flows and breccias with minor andesitic tuffs of the Ootsa Lake Group are the dominant rock units. A small subcrop of quartz monzonite was observed in one area. Pyroxenite and gabbro float was also located over a small area.

The basalt units are fine to medium grained, dark green to maroon in colour and contain euhedral white feldspar phenocrysts. Dark green augite phenocrysts, calcite and epidote crystals are observed within this unit locally.

Prospecting on the western portion of the claims relied on float material due to extensive overburden cover. Highly clay-altered, light brown rhyolite or andesite tuff with disseminated pyrite to 5% was noticed throughout this area.

PREVIOUS WORK

The Fawnie claims were staked in 1989 and 20 line-kilometres of grid established that year. Soil geochemical samples were collected at 50-metre intervals on lines spaced 100 metres apart. A majority of the property was geologically mapped and several rock samples were collected.

1990 WORK PROGRAM

The 1990 work program was conducted July 23 to 31, 1990 from a fly camp established on the property. A total of 375 soil samples and five rock samples were collected from 17 line-kilometres established in two grid areas. Grid A, established in 1989, was extended by six-line kilometres 400 metres to the south. A new grid, Grid B, was established over a ridge in the centre of the property totalling 11 line-kilometres. Soils samples were collected from the "B" horizon where possible at 50-metre intervals on lines spaced 100 metres apart. Rock samples were grabs of either bedrock or float material. All samples were analyzed for 30 elements using ICP techniques and for gold by geochemical AA methods at Acme Analytical Laboratories Ltd., Vancouver, B.C. The

principle elements of interest (Cu, Pb, Zn, Ag, Ni, Mn, As, Ca, Au) along with field notes are provided in Appendix I.

RESULTS

Results of the extension to Grid A were moderately encouraging. A +20 ppb gold anomaly, 200 metres wide was extended 250 metres to the south (Figure 4). A weak arsenic anomaly was outlined over a 200-metre by 300-metre area, with a high value of 41 ppb As (Figure 5). Zinc returned moderately anomalous results with a +135 ppm Zn anomaly over a 250-metre by 600-metre area (Figure 6). Silver concentrations were moderately to highly anomalous with at +1.0 ppm anomaly occurring over a 550-metre by 500-metre area and open to the south. A high value of 13.3 ppm Ag was returned from this area (Figure 7).

Results of geochemical sampling on Grid B were mixed. Only five samples were anomalous in gold, one sample returned 275 ppb Au (Figure 4). No samples from this grid area were anomalous with respect to arsenic. Zinc concentrations returned several strong anomalies, the largest of which is 300 metres by 450 metres with a high value of 5,196 ppm Zn and is open to the north (Figure 6). Silver concentrations were moderately anomalous over a 200-metre by 400-metre area. A high value of 6.8 ppm Ag was obtained and the anomaly is open to the north (Figure 7).

CONCLUSIONS AND RECOMMENDATIONS

Results of the 1990 soil geochemical program on the Fawnie prospect were moderately encouraging. Anomalous areas of silver, gold and arsenic were outlined on both grids. Arsenic returned anomalous concentrations on Grid A only.

The silver and zinc anomalies of Grid B are especially encouraging as this grid is situated across a valley and therefore the soil profiles reflect a more proximal source of enrichment than for Grid A.

Recommendations for the prospect include the expansion of the grid areas by 20 line-kilometres and trenching by back-hoe areas of anomalous float and soil samples to determine a bedrock source.

DISBURSEMENTS

Project disbursements for 1990 were \$19,072.23 as shown below.

Salaries

G. Goodall - Geologist	8 days @ \$360	2,880.00	
J. McRae - Sampler	8 days @ \$230	1,840.00	
R. Roe - Sampler	8 days @ \$240	1,920.00	
J. Goodall - Sampler	8 days @ \$230	<u>1,840.00</u>	\$ 8,480.00

Accommodation & Board

32 mandays @ \$50/day			1,600.00
-----------------------	--	--	----------

Helicopter Support

5.3 hours @ \$712.64/hour			3,776.98
---------------------------	--	--	----------

Geochemical Analyses

375 soil samples @ \$10.10	3,787.50		
5 rock samples @ \$12.25	<u>61.25</u>		3,848.75

Vehicle Rental & Maintenance

8 days @ \$50/day			400.00
-------------------	--	--	--------

Field Supplies & Freight			216.50
--------------------------	--	--	--------

Report Preparation			<u>750.00</u>
--------------------	--	--	---------------

Total Disbursements			\$ <u>19,072.23</u>
----------------------------	--	--	----------------------------

Prepared by:

FOX GEOLOGICAL CONSULTANTS LTD.




Geoff N. Goodall, B.Sc.

April 18, 1991

CERTIFICATE

I, Geoffrey N. Goodall, of the City of Vancouver, British Columbia, do hereby certify that:

1. I graduated from the University of British Columbia in 1984 with a Bachelor of Science degree in geology.
2. I have been practising my profession as a geologist since 1984.
3. I am a Fellow of the Geological Association of Canada.



Geoffrey N. Goodall, B.Sc.

April 18, 1991

A P P E N D I X I
Geochemical Analysis

Project 138
FAWN Property
1990 Geochemical Results

Sample	Cu (ppm)	Pb (ppm)	Zn (ppm)	Ag (ppm)	Ca (%)	Ni (ppm)	Co (ppm)	Fe (%)	As (ppm)	Au (ppb)	Sample Type	Remarks	Grid	North	East
22639	15	14	66	0.1	2.12	10	7	2.70	10	1	GRAB	POLYLITHIC CRYSTAL TUFF	A		
23094	1	338	165	3.2	0.03	2	1	0.59	30	1	GRAB	BOULDER IN TRENCH SILICIOUS RHY.W/PY	A	11500	10300
23098	13	14	66	0.4	0.31	6	4	3.84	5	1	GRAB	DARK GREEN VOLCANIC BX.W/PY.	A	11500	10450
22638	0	0	0	0.0	0.00	0	0	0.00	0	0	SILT	CREEK NEAR SOUTH CLAIM LINE.	A		
22635	16	41	159	0.6	0.22	12	8	3.23	15	3	SOIL	CLAIM POST 4N-0E FAWN 1-2	A	4	
26140	7	14	60	0.3	0.18	9	5	2.69	8	1	SOIL		A	9800	9500
27938	13	25	83	0.5	0.16	5	6	3.33	16	2	SOIL	B.L.	A	10800	10000
27937	14	32	159	0.9	0.15	6	5	3.66	14	5	SOIL		A	10800	10050
27936	28	40	131	2.7	0.35	9	9	3.35	17	9	SOIL		A	10800	10100
27935	13	48	89	1.3	0.14	6	4	2.50	14	16	SOIL		A	10800	10150
27934	14	47	110	2.7	0.11	7	5	2.36	16	7	SOIL		A	10800	10200
27933	17	36	102	1.0	0.15	10	6	3.51	25	29	SOIL		A	10800	10250
27932	22	74	147	1.4	0.15	12	10	3.76	41	26	SOIL		A	10800	10300
27931	12	55	111	0.9	0.13	7	5	4.15	23	12	SOIL	TOP OF CREEK GULLEY	A	10800	10350
27930	17	62	204	1.9	0.17	13	7	3.27	30	11	SOIL	NEXT TO CREEK	A	10800	10400
27929	21	42	114	0.7	0.10	6	5	3.57	21	13	SOIL	SIDE OF CREEK GULLEY	A	10800	10450
27928	5	20	45	0.5	0.15	3	2	1.20	4	2	SOIL	TOP OF CREEK GULLEY	A	10800	10500
27927	10	31	126	2.0	0.57	11	6	2.46	7	9	SOIL		A	10800	10550
27926	18	39	152	2.4	1.12	12	9	3.15	10	36	SOIL		A	10800	10600
27925	13	32	99	2.2	0.46	10	6	2.57	10	9	SOIL		A	10800	10650
27924	19	33	119	3.4	0.85	14	11	3.01	8	2	SOIL		A	10800	10700
27923	16	42	142	2.4	0.99	12	11	3.12	10	6	SOIL		A	10800	10750
27922	10	29	83	1.0	0.33	10	6	2.00	3	9	SOIL		A	10800	10800
27921	10	29	90	1.0	0.25	9	5	1.96	3	3	SOIL		A	10800	10850
27920	9	39	136	1.3	0.22	13	6	2.08	7	4	SOIL		A	10800	10900
27919	10	31	141	1.0	0.36	16	7	1.91	4	3	SOIL		A	10800	10950
27917	14	26	109	0.1	0.37	12	9	2.56	8	5	SOIL		A	10800	11000
27918	9	28	95	1.1	0.39	11	6	1.93	3	3	SOIL		A	10800	11000
27916	10	22	46	0.3	0.09	6	4	2.93	5	1	SOIL		A	10800	11100
27915	19	28	122	1.2	0.43	19	8	2.00	4	2	SOIL		A	10800	11150
27914	18	23	170	1.0	0.33	19	8	2.48	5	1	SOIL		A	10800	11200
27913	16	28	229	0.6	0.45	13	8	2.63	3	5	SOIL		A	10800	11250
27912	10	21	97	0.3	0.27	10	5	2.07	6	2	SOIL		A	10800	11300
27911	10	25	93	0.1	0.36	9	6	1.89	3	2	SOIL		A	10800	11350
27910	14	28	126	0.2	0.41	11	7	2.56	6	2	SOIL		A	10800	11400
27909	22	21	137	1.4	0.82	10	9	2.21	2	2	SOIL		A	10800	11450
27908	27	23	136	1.1	0.37	13	11	4.36	6	1	SOIL	EOL	A	10800	11500
24983	5	32	27	0.8	0.09	2	1	1.10	2	4	SOIL	B.L.	A	10900	10000
24984	11	32	67	0.5	0.13	5	5	3.60	16	66	SOIL		A	10900	10050
24985	8	26	72	0.2	0.12	5	4	2.58	10	5	SOIL		A	10900	10100
24986	20	41	97	1.5	0.14	7	6	2.85	22	15	SOIL		A	10900	10150
24987	12	49	141	1.1	0.32	6	12	2.20	9	17	SOIL		A	10900	10200
24988	21	55	230	6.8	0.23	13	6	3.11	19	9	SOIL		A	10900	10250
24989	12	52	81	1.4	0.12	7	4	2.26	15	8	SOIL		A	10900	10300
24990	10	49	87	0.8	0.08	5	3	2.49	16	10	SOIL		A	10900	10350
24991	10	50	85	0.4	0.08	5	4	2.34	20	28	SOIL		A	10900	10400
24992	15	55	94	1.4	0.11	6	4	2.71	29	12	SOIL	TOP OF CREEK GULLEY	A	10900	10450
24993	15	79	197	2.0	0.12	7	4	2.64	26	14	SOIL	CREEK GULLEY	A	10900	10500
24994	16	93	145	0.6	0.19	6	4	2.52	41	26	SOIL	NEXT TO CREEK	A	10900	10550
24995	17	47	103	0.2	0.18	8	6	2.83	13	10	SOIL		A	10900	10600
24996	28	45	156	6.1	0.83	12	9	2.77	13	16	SOIL		A	10900	10650
24997	38	48	144	5.2	1.19	10	8	2.81	15	4	SOIL		A	10900	10700
24998	9	37	120	0.3	0.36	9	6	2.12	6	1	SOIL		A	10900	10750

Sample	Cu (ppm)	Pb (ppm)	Zn (ppm)	Ag (ppm)	Ca (%)	Ni (ppm)	Co (ppm)	Fe (%)	As (ppm)	Au (ppb)	Sample Type	Remarks	Grid	North	East
30063	11	20	62	0.1	0.27	7	5	2.97	5	1	SOIL		B	9600	10500
30084	22	20	110	1.9	1.77	11	6	2.32	3	2	SOIL		B	9700	9500
30083	17	25	81	1.3	0.63	12	7	2.30	4	2	SOIL		B	9700	9550
30082	11	18	33	1.0	0.14	7	4	1.50	3	3	SOIL		B	9700	9600
30081	11	22	73	0.3	0.17	10	4	1.80	2	1	SOIL		B	9700	9650
30080	6	20	30	0.1	0.08	1	2	1.20	2	1	SOIL		B	9700	9700
30079	10	25	98	0.2	0.14	9	5	2.51	8	2	SOIL		B	9700	9750
30078	87	412	918	0.7	0.24	11	7	2.53	6	5	SOIL		B	9700	9800
30077	17	136	108	0.1	0.15	6	3	1.74	3	2	SOIL		B	9700	9850
30076	8	20	53	0.1	0.09	4	2	1.62	3	1	SOIL		B	9700	9900
30075	5	36	68	0.2	0.09	5	3	2.11	4	4	SOIL		B	9700	9950
30074	8	24	58	0.5	0.11	6	4	2.82	4	1	SOIL		B	9700	10000
30073	10	10	66	0.6	0.18	7	6	4.04	2	2	SOIL		B	9700	10050
30072	10	14	31	0.3	0.23	3	2	1.51	2	2	SOIL		B	9700	10100
30071	9	11	72	0.2	0.56	7	7	2.53	4	1	SOIL		B	9700	10150
30070	10	17	85	0.1	0.41	9	7	2.54	5	1	SOIL		B	9700	10200
30069	23	38	135	0.1	0.16	11	10	4.25	8	1	SOIL		B	9700	10250
30068	10	19	69	0.3	0.24	7	6	3.18	5	2	SOIL		B	9700	10300
30067	19	13	281	0.1	0.67	5	5	1.71	3	1	SOIL		B	9700	10350
30066	7	15	60	0.1	0.24	5	4	2.42	4	6	SOIL		B	9700	10400
30065	9	18	101	0.1	0.15	7	7	3.68	9	1	SOIL		B	9700	10450
30064	4	20	46	0.1	0.15	3	4	2.43	3	1	SOIL		B	9700	10500
26141	65	30	368	0.5	0.83	23	13	3.84	14	1	SOIL		B	9800	9550
26142	10	16	89	0.4	0.15	12	6	2.63	6	264	SOIL		B	9800	9600
26143	7	19	69	0.3	0.12	10	5	2.13	4	13	SOIL		B	9800	9650
26144	13	18	99	0.2	0.30	13	7	2.60	5	3	SOIL		B	9800	9700
26145	21	14	132	0.2	0.24	14	9	2.85	7	3	SOIL		B	9800	9750
26146	10	21	101	0.1	0.23	12	6	2.38	5	216	SOIL		B	9800	9800
26147	10	27	459	0.4	0.25	14	8	3.00	4	9	SOIL		B	9800	9850
26148	79	442	5802	0.2	0.45	15	8	2.89	12	1	SOIL		B	9800	9900
26149	15	123	310	0.5	0.09	10	6	3.26	8	2	SOIL		B	9800	9950
26150	11	39	100	0.6	0.13	10	6	3.19	7	4	SOIL	B.L	B	9800	10000
27961	10	36	57	0.7	0.14	6	4	2.35	6	1	SOIL		B	9800	10050
27962	23	50	164	0.5	0.38	12	7	3.04	8	1	SOIL		B	9800	10100
27963	11	25	111	0.4	0.19	9	6	2.53	4	1	SOIL		B	9800	10150
27964	20	29	400	0.5	0.37	12	7	3.05	9	2	SOIL		B	9800	10200
27965	13	21	101	0.7	0.26	10	6	4.19	6	1	SOIL		B	9800	10250
27966	12	15	113	0.5	0.16	14	7	4.25	9	1	SOIL		B	9800	10300
27967	7	19	66	0.1	0.11	8	6	3.00	9	7	SOIL		B	9800	10350
27968	15	19	83	0.2	0.14	7	6	3.16	7	2	SOIL		B	9800	10400
27969	11	57	151	0.1	0.16	5	6	2.74	6	3	SOIL		B	9800	10450
27970	9	23	92	0.2	0.17	7	7	3.38	9	5	SOIL		B	9800	10500
26139	8	13	65	0.3	0.30	11	5	2.13	6	3	SOIL		B	9900	9500
26138	15	14	82	0.2	0.14	13	5	3.07	15	6	SOIL		B	9900	9550
26137	19	20	352	0.3	0.20	12	6	2.29	5	1	SOIL		B	9900	9600
26136	11	17	50	0.1	0.13	8	4	2.50	12	1	SOIL		B	9900	9650
26135	11	19	54	0.1	0.16	8	4	3.27	18	1	SOIL		B	9900	9700
26134	12	13	64	0.1	0.16	11	5	3.35	14	2	SOIL		B	9900	9750
26133	12	22	56	0.2	0.11	11	5	2.40	8	2	SOIL		B	9900	9800
26132	19	21	83	0.3	0.13	13	6	2.82	9	3	SOIL		B	9900	9850
26131	11	22	79	0.2	0.14	11	5	2.90	11	4	SOIL		B	9900	9900
26130	15	20	95	0.1	0.11	15	6	3.18	16	4	SOIL		B	9900	9950
26129	15	43	102	0.1	0.15	12	6	3.55	11	5	SOIL		B	9900	10000
26128	17	18	112	0.2	0.19	15	7	3.19	15	1	SOIL		B	9900	10050
26127	11	21	79	0.1	0.10	10	5	3.16	12	2	SOIL		B	9900	10100
26126	13	25	103	0.1	0.19	10	5	2.71	9	4	SOIL		B	9900	10150
26125	19	48	205	0.1	0.28	11	6	2.45	9	3	SOIL		B	9900	10200

Sample	Cu (ppm)	Pb (ppm)	Zn (ppm)	Ag (ppm)	Ca (%)	N1 (ppm)	Co (ppm)	Fe (%)	As (ppm)	Au (ppb)	Sample Type	Remarks	Grid	North	East
26124	12	20	83	0.1	0.18	12	6	3.45	10	2	SOIL		B	9900	10250
26123	8	16	84	0.1	0.27	9	5	2.64	4	1	SOIL		B	9900	10300
26122	17	21	117	0.1	0.14	13	6	3.00	10	1	SOIL		B	9900	10350
26121	14	44	358	0.1	0.15	10	6	3.08	9	3	SOIL		B	9900	10400
26120	12	20	111	0.1	0.21	8	5	2.80	7	3	SOIL		B	9900	10450
26119	9	23	110	0.2	0.20	7	4	3.15	7	2	SOIL		B	9900	10500
26102	11	16	58	0.2	0.10	9	4	3.23	9	3	SOIL		B	10000	9700
26103	8	19	55	0.1	0.09	8	4	2.77	6	7	SOIL		B	10000	9750
26104	9	17	50	0.1	0.14	10	4	2.80	9	2	SOIL		B	10000	9800
26105	15	29	70	0.4	0.10	11	5	3.21	16	3	SOIL		B	10000	9850
26106	12	28	63	0.2	0.12	11	5	3.02	9	27	SOIL		B	10000	9900
26107	34	28	308	0.2	0.13	10	6	2.34	9	275	SOIL		B	10000	9950
26108	21	63	142	0.3	0.09	9	4	2.77	9	13	SOIL		B	10000	10000
26109	15	31	100	0.1	0.09	13	6	2.54	8	2	SOIL		B	10000	10050
26110	16	33	98	0.6	0.12	11	5	3.24	10	1	SOIL		B	10000	10100
26111	16	29	107	0.1	0.15	11	7	2.81	8	4	SOIL		B	10000	10150
26112	13	55	100	0.1	0.14	10	5	1.77	4	2	SOIL		B	10000	10200
26113	10	23	94	0.1	0.20	9	6	2.09	3	4	SOIL		B	10000	10250
26114	11	40	87	0.2	0.14	7	4	2.42	6	2	SOIL		B	10000	10300
26115	10	45	123	0.2	0.13	7	4	2.72	9	1	SOIL		B	10000	10350
26116	11	27	60	0.2	0.11	7	4	2.93	5	1	SOIL		B	10000	10400
26117	17	38	104	0.1	0.15	11	7	3.34	11	2	SOIL		B	10000	10450
26118	13	25	107	0.3	0.15	10	6	3.48	5	2	SOIL		B	10000	10500
30042	6	18	36	0.3	0.08	5	3	2.22	6	1	SOIL		B	10100	9500
30041	10	20	29	0.7	0.07	3	2	1.30	5	2	SOIL		B	10100	9550
30040	7	17	63	0.5	0.10	9	5	2.86	8	24	SOIL		B	10100	9600
30039	12	18	47	0.3	0.10	8	3	2.31	7	1	SOIL		B	10100	9650
30038	10	18	27	0.4	0.13	4	2	1.41	4	1	SOIL		B	10100	9700
30037	17	12	62	1.1	0.28	14	7	2.56	10	3	SOIL		B	10100	9750
30036	8	18	29	0.5	0.09	4	2	1.24	5	2	SOIL		B	10100	9800
30035	10	19	32	0.4	0.13	3	1	0.82	2	2	SOIL		B	10100	9850
30034	6	26	26	0.5	0.09	3	1	0.80	2	3	SOIL		B	10100	9900
30033	7	17	69	0.4	0.13	8	4	2.02	6	1	SOIL		B	10100	9950
30032	6	28	103	0.8	0.15	4	2	1.29	2	1	SOIL		B	10100	10000
30031	13	33	99	0.1	0.11	9	5	2.87	8	3	SOIL		B	10100	10050
30030	11	29	59	0.2	0.09	7	3	2.58	7	3	SOIL		B	10100	10100
30029	43	24	46	1.5	0.09	14	5	1.67	2	1	SOIL		B	10100	10150
30028	11	37	59	0.1	0.12	6	3	2.08	5	1	SOIL		B	10100	10200
30027	12	32	97	0.1	0.11	12	6	3.24	17	4	SOIL		B	10100	10250
30026	10	30	42	0.2	0.15	5	4	1.97	2	2	SOIL		B	10100	10300
30025	7	23	70	0.4	0.15	8	4	2.51	10	4	SOIL		B	10100	10350
30024	7	20	39	0.1	0.11	4	2	1.33	4	4	SOIL		B	10100	10400
30023	8	28	75	0.1	0.14	7	4	2.73	8	2	SOIL		B	10100	10450
30022	10	24	46	0.4	0.30	5	3	2.01	2	2	SOIL		B	10100	10500
30021	13	17	63	1.7	0.13	8	5	3.17	8	20	SOIL		B	10200	9500
30020	6	16	48	0.4	0.11	6	4	2.39	7	1	SOIL		B	10200	9550
30019	19	18	164	0.5	0.75	10	6	2.46	6	3	SOIL		B	10200	9600
30018	103	27	214	6.8	1.38	12	8	2.63	14	3	SOIL		B	10200	9650
30017	11	13	70	0.3	0.16	8	5	1.82	2	1	SOIL	9750-NO SAMPLE - SWAMP	B	10200	9700
30016	14	18	123	0.7	0.23	11	6	2.29	2	2	SOIL		B	10200	9800
30015	31	44	300	1.7	0.20	12	4	2.17	7	2	SOIL		B	10200	9850
30014	22	16	518	0.8	0.76	9	6	1.83	2	1	SOIL		B	10200	9900
30013	83	16	242	2.6	2.07	8	3	0.94	2	3	SOIL		B	10200	9950
30012	8	42	48	0.1	0.14	5	2	0.94	2	1	SOIL		B	10200	10000
30011	9	15	48	0.1	0.12	5	4	1.41	3	1	SOIL		B	10200	10050
30010	9	22	67	0.3	0.11	8	5	2.19	2	1	SOIL		B	10200	10100
30009	9	32	90	0.1	0.11	8	4	1.66	2	1	SOIL		B	10200	10150

Sample	Cu (ppm)	Pb (ppm)	Zn (ppm)	Ag (ppm)	Ca (%)	Ni (ppm)	Co (ppm)	Fe (%)	As (ppm)	Au (ppb)	Sample Type	Remarks	Grid	North	East
30008	6	21	36	0.1	0.10	5	3	1.58	2	1	SOIL		B	10200	10200
30007	17	27	61	0.8	0.16	12	8	2.71	2	1	SOIL		B	10200	10250
30006	13	24	33	0.2	0.11	7	4	2.50	4	1	SOIL		B	10200	10300
29450	10	26	37	0.7	0.10	8	4	1.69	6	1	SOIL		B	10200	10350
29449	6	24	10	0.4	0.11	4	2	1.44	2	1	SOIL		B	10200	10400
29448	8	31	39	0.4	0.14	8	6	2.75	5	2	SOIL		B	10200	10450
29447	7	35	45	0.6	0.13	4	4	2.87	2	1	SOIL		B	10200	10500
29426	12	22	50	0.7	0.10	9	6	3.31	13	1	SOIL		B	10300	9500
29427	13	30	89	0.6	0.17	16	10	3.70	7	2	SOIL		B	10300	9550
29428	12	25	61	1.0	0.10	9	5	2.17	7	2	SOIL		B	10300	9600
29429	15	9	47	5.4	0.22	9	4	0.98	2	2	SOIL		B	10300	9650
29430	20	9	40	3.6	0.32	7	5	1.12	2	2	SOIL		B	10300	9700
29431	20	6	64	2.8	0.49	8	4	1.11	2	2	SOIL		B	10300	9750
29432	19	12	132	0.9	0.75	8	6	2.07	2	2	SOIL		B	10300	9800
29433	19	14	48	2.0	0.45	8	5	1.44	3	1	SOIL		B	10300	9850
29434	42	8	798	1.6	1.70	16	9	3.32	2	1	SOIL		B	10300	9900
29435	42	14	939	0.4	0.88	11	7	2.67	6	2	SOIL		B	10300	9950
29436	52	14	477	2.9	0.96	12	7	2.25	2	2	SOIL		B	10300	10000
29437	78	24	360	3.9	1.76	8	6	1.68	2	1	SOIL		B	10300	10050
29438	107	65	356	1.9	1.51	6	4	1.55	2	1	SOIL		B	10300	10100
29439	23	67	91	0.3	0.21	5	2	1.21	3	1	SOIL		B	10300	10150
29440	54	17	115	0.6	0.21	7	5	1.78	2	1	SOIL		B	10300	10200
29441	23	17	73	0.6	0.13	9	5	2.60	6	3	SOIL		B	10300	10250
29442	11	21	33	0.2	0.13	5	3	1.43	2	1	SOIL		B	10300	10300
29443	13	30	66	0.8	0.14	7	5	2.36	2	1	SOIL		B	10300	10350
29444	13	21	46	0.3	0.13	9	4	2.14	4	1	SOIL		B	10300	10400
29445	10	25	52	0.4	0.12	8	5	2.04	4	1	SOIL		B	10300	10450
29446	5	13	1	0.1	0.09	3	2	0.87	5	2	SOIL		B	10300	10500
29425	13	19	82	0.6	0.15	16	9	3.42	5	2	SOIL		B	10400	9500
29424	10	32	29	0.4	0.13	8	3	1.11	3	1	SOIL		B	10400	9550
29423	13	26	70	0.9	0.18	11	6	2.15	11	3	SOIL		B	10400	9600
29422	11	22	217	2.6	0.20	9	8	5.21	5	3	SOIL		B	10400	9650
29421	10	26	65	3.8	0.24	7	3	1.20	2	4	SOIL	9750 NO SAMPLE-SWAMP	B	10400	9700
29420	21	14	409	1.1	0.66	9	7	2.09	2	2	SOIL		B	10400	9800
29419	15	7	210	0.6	0.44	8	6	2.41	4	1	SOIL		B	10400	9850
29418	45	16	225	2.3	0.77	16	8	2.95	3	4	SOIL		B	10400	9900
29417	47	10	193	1.0	0.52	7	4	0.96	7	5	SOIL		B	10400	9950
29416	76	14	561	1.2	1.44	9	8	1.94	3	1	SOIL		B	10400	10000
29415	140	19	786	0.9	0.91	10	6	1.89	2	2	SOIL		B	10400	10050
29414	72	9	1362	0.9	2.88	8	6	1.42	3	2	SOIL		B	10400	10100
29413	192	27	5196	0.2	1.92	12	7	2.53	6	2	SOIL		B	10400	10150
29412	9	35	140	0.4	0.10	5	4	1.76	2	5	SOIL		B	10400	10200
29411	12	37	104	0.2	0.12	8	5	2.69	3	2	SOIL		B	10400	10250
29410	6	25	48	0.6	0.12	5	3	1.62	2	1	SOIL		B	10400	10300
29409	60	30	148	0.6	0.15	6	3	1.70	2	1	SOIL		B	10400	10350
29408	13	39	65	0.7	0.18	6	4	2.12	4	1	SOIL		B	10400	10400
29407	21	21	73	0.8	0.19	14	9	2.65	5	1	SOIL		B	10400	10450
29406	15	24	81	0.4	0.14	8	6	2.43	4	7	SOIL		B	10400	10500
29385	9	19	59	0.4	0.09	12	8	4.87	10	2	SOIL		B	10500	9500
29386	16	25	88	0.1	0.15	15	11	6.12	8	4	SOIL		B	10500	9550
29387	14	23	80	0.2	0.21	13	7	2.96	7	2	SOIL		B	10500	9600
29388	17	24	68	2.2	0.39	9	5	1.38	3	2	SOIL		B	10500	9650
29389	12	22	92	0.6	0.25	13	7	2.42	4	1	SOIL		B	10500	9700
29390	15	20	255	0.8	0.61	13	8	2.85	2	1	SOIL		B	10500	9750
29391	21	17	177	0.7	0.31	12	7	2.43	2	5	SOIL		B	10500	9800
29392	27	3	185	0.4	0.40	10	7	2.89	2	3	SOIL		B	10500	9850
29393	17	13	82	0.2	0.36	9	8	2.90	4	2	SOIL		B	10500	9900

Sample	Cu (ppm)	Pb (ppm)	Zn (ppm)	Ag (ppm)	Ca (%)	Ni (ppm)	Co (ppm)	Fe (%)	As (ppm)	Au (ppb)	Sample Type	Remarks	Grid	North	East
27976	5	11	36	0.1	0.12	8	5	2.80	4	2	SOIL		B	9400	9750
27975	10	14	47	0.2	0.13	8	6	2.94	5	3	SOIL		B	9400	9800
27974	10	12	76	0.1	0.15	13	7	3.34	8	3	SOIL	TALUS	B	9400	9850
27973	7	25	93	0.1	0.20	7	7	4.24	4	1	SOIL	TALUS	B	9400	9900
27972	13	10	79	0.1	0.24	13	9	4.50	14	2	SOIL		B	9400	9950
27971	15	40	106	0.3	0.12	8	7	3.67	6	1	SOIL	ROCKY B.L.	B	9400	10000
27992	11	28	99	0.1	0.12	8	8	4.61	10	2	SOIL	ROCKY	B	9400	10050
27993	12	33	156	0.2	0.12	12	8	3.99	24	2	SOIL	ROCKY	B	9400	10100
27994	11	25	109	0.3	0.15	13	10	5.08	15	2	SOIL		B	9400	10150
27995	13	23	58	0.1	0.15	14	9	3.52	9	7	SOIL		B	9400	10200
27996	19	22	76	0.1	0.20	21	14	4.60	17	3	SOIL		B	9400	10250
27997	10	14	59	0.2	0.12	12	6	2.95	9	3	SOIL		B	9400	10300
27998	14	22	114	0.1	0.41	9	7	2.50	8	1	SOIL		B	9400	10350
27999	10	13	95	0.2	0.13	14	9	4.46	10	2	SOIL		B	9400	10400
28000	11	22	62	0.2	0.13	12	9	4.73	7	1	SOIL		B	9400	10450
30101	9	9	64	0.2	0.14	7	5	2.91	2	2	SOIL		B	9400	10500
27982	22	14	111	0.7	1.06	17	10	3.35	14	1	SOIL		B	9500	9500
27983	11	17	76	0.2	0.43	13	7	2.14	5	2	SOIL		B	9500	9550
27984	14	19	82	0.3	0.18	14	9	2.78	7	2	SOIL		B	9500	9600
27985	6	31	72	0.2	0.13	9	5	1.88	4	1	SOIL		B	9500	9650
27986	10	19	76	0.2	0.12	13	8	3.11	10	1	SOIL	ROCKY	B	9500	9700
27987	12	23	84	0.2	0.10	11	9	6.00	22	2	SOIL	ROCKY	B	9500	9750
27988	9	20	69	0.2	0.10	9	6	3.16	10	1	SOIL	ROCKY	B	9500	9800
27989	12	23	57	0.2	0.11	10	5	2.67	10	1	SOIL	ROCKY	B	9500	9850
27990	8	17	95	0.1	0.13	11	8	3.92	11	1	SOIL		B	9500	9900
27991	10	11	60	0.1	0.14	8	6	2.91	7	1	SOIL		B	9500	9950
30112	8	14	85	0.1	0.23	9	7	3.39	4	2	SOIL	B. L.	B	9500	10000
30111	15	13	90	0.2	0.23	11	8	3.46	4	1	SOIL	TALUS	B	9500	10050
30110	20	32	85	0.3	0.15	9	8	4.88	8	2	SOIL	ROCKY	B	9500	10100
30109	17	35	94	0.6	0.20	7	8	5.14	10	1	SOIL	ROCKY	B	9500	10150
30108	9	18	87	0.2	0.18	9	8	3.96	10	1	SOIL		B	9500	10200
30107	10	26	132	0.1	0.18	7	7	4.15	8	2	SOIL	ROCKY	B	9500	10250
30106	27	20	208	0.1	0.55	13	11	4.23	12	1	SOIL		B	9500	10300
30105	10	18	82	0.2	0.17	8	6	4.32	5	6	SOIL		B	9500	10350
30104	26	32	129	0.2	0.40	10	7	2.90	10	1	SOIL		B	9500	10400
30103	39	37	381	0.2	0.53	11	8	3.01	9	4	SOIL	POOR SOIL-ROCKY	B	9500	10450
30102	22	20	120	0.5	0.33	14	7	3.51	8	1	SOIL		B	9500	10500
30043	18	14	84	1.2	1.17	11	6	1.64	4	4	SOIL		B	9600	9500
30044	16	21	49	1.1	0.14	7	3	1.34	10	2	SOIL		B	9600	9550
30045	15	21	72	0.5	0.11	13	8	2.48	11	3	SOIL		B	9600	9600
30046	2	20	30	0.2	0.09	5	2	1.00	4	3	SOIL		B	9600	9650
30047	2	17	33	0.1	0.08	6	3	1.22	7	2	SOIL		B	9600	9700
30048	50	118	1118	0.1	0.56	11	7	2.08	5	2	SOIL		B	9600	9750
30049	15	23	85	0.2	0.12	6	2	1.69	10	1	SOIL		B	9600	9800
30050	8	113	88	0.4	0.27	5	3	2.12	6	14	SOIL		B	9600	9850
30051	13	21	75	0.5	0.16	13	10	3.94	8	1	SOIL		B	9600	9900
30052	17	19	48	0.8	0.13	6	5	3.00	4	6	SOIL		B	9600	9950
30053	10	14	61	0.6	0.13	10	7	3.02	4	4	SOIL		B	9600	10000
30054	7	14	63	0.4	0.21	7	6	2.96	2	3	SOIL		B	9600	10050
30055	9	15	68	0.4	0.20	8	6	3.84	5	2	SOIL		B	9600	10100
30056	14	16	64	0.5	0.23	7	6	3.93	2	3	SOIL		B	9600	10150
30057	11	16	75	0.5	0.22	6	6	3.91	5	1	SOIL		B	9600	10200
30058	9	19	53	0.1	0.14	5	5	3.29	7	1	SOIL		B	9600	10250
30059	10	17	66	0.2	0.16	12	8	3.26	6	1	SOIL		B	9600	10300
30060	11	14	86	0.1	0.27	14	7	3.55	4	1	SOIL		B	9600	10350
30061	12	27	147	0.1	0.25	11	8	3.50	14	2	SOIL		B	9600	10400
30062	7	20	75	0.1	0.13	7	6	3.23	6	1	SOIL		B	9600	10450

Sample	Cu (ppm)	Pb (ppm)	Zn (ppm)	Ag (ppm)	Ca (%)	Ni (ppm)	Co (ppm)	Fe (%)	As (ppm)	Au (ppb)	Sample Type	Remarks	Grid	North	East
24999	14	37	135	0.9	0.29	11	7	2.45	6	6	SOIL		A	10900	10800
25000	9	35	105	1.0	0.25	11	6	2.15	4	10	SOIL		A	10900	10850
27896	11	29	108	0.9	0.28	10	5	2.16	7	6	SOIL		A	10900	10900
27897	12	25	147	1.0	0.50	13	7	2.57	8	3	SOIL		A	10900	10950
27898	14	31	149	1.3	0.55	14	7	2.28	5	2	SOIL		A	10900	11000
27899	14	27	143	1.0	0.71	13	8	2.50	13	4	SOIL		A	10900	11050
27900	12	22	108	0.8	0.39	13	7	2.18	5	11	SOIL		A	10900	11100
27901	14	28	152	0.4	0.62	15	10	2.95	6	1	SOIL		A	10900	11150
27902	6	23	49	0.1	0.09	7	4	3.49	5	1	SOIL		A	10900	11200
27903	41	17	250	0.8	0.60	9	5	1.22	9	4	SOIL	SWAMP-CLEARING	A	10900	11250
27904	5	34	55	0.1	0.14	6	2	0.96	2	1	SOIL	11300E NO SAMPLE-SWAMP	A	10900	11350
27905	17	33	165	0.3	0.35	15	8	2.70	9	2	SOIL		A	10900	11400
27906	19	39	195	0.3	0.66	15	9	2.93	13	2	SOIL		A	10900	11450
27907	16	26	118	0.6	0.68	14	11	2.93	6	3	SOIL	E.O.L.	A	10900	11500
24955	19	38	170	0.4	0.81	13	8	2.75	17	7	SOIL		A	11000	1145
24982	13	54	62	0.5	0.09	4	3	3.34	33	11	SOIL	B.L	A	11000	10050
24981	10	65	72	1.9	0.07	3	3	2.30	28	19	SOIL		A	11000	10100
24980	6	45	60	0.4	0.10	4	3	1.79	9	10	SOIL		A	11000	10150
24979	9	43	53	0.9	0.09	5	3	1.99	8	11	SOIL		A	11000	10200
24978	12	46	74	0.8	0.11	5	4	1.81	10	15	SOIL		A	11000	10250
24977	23	35	188	3.7	1.21	8	9	2.64	25	18	SOIL		A	11000	10300
24976	12	48	63	1.4	0.22	4	4	2.70	19	5	SOIL		A	11000	10350
24975	13	64	102	1.0	0.11	5	3	1.97	21	8	SOIL		A	11000	10400
24974	12	48	82	0.7	0.09	5	4	2.80	19	15	SOIL		A	11000	10450
24973	7	51	86	0.7	0.09	5	3	1.58	6	8	SOIL		A	11000	10500
24972	7	40	36	1.0	0.07	4	3	2.27	10	8	SOIL		A	11000	10550
24971	3	40	50	0.5	0.13	4	2	1.10	3	11	SOIL	TOP OF GULLEY	A	11000	10600
24970	19	33	89	0.7	0.18	11	7	2.58	19	26	SOIL	NEXT TO CREEK	A	11000	10650
24969	14	67	119	1.6	0.13	6	4	2.30	20	107	SOIL		A	11000	10700
24968	24	48	210	4.2	1.17	13	15	3.60	20	6	SOIL		A	11000	10750
24967	16	48	110	2.6	0.45	8	6	1.87	9	4	SOIL		A	11000	10800
24966	16	46	143	2.8	0.72	10	7	2.05	14	18	SOIL		A	11000	10850
24965	21	36	140	2.5	0.53	14	14	2.62	12	2	SOIL		A	11000	10900
24964	14	33	108	1.3	0.34	10	7	2.16	12	18	SOIL		A	11000	10950
24963	11	24	74	0.6	0.26	9	5	1.85	10	6	SOIL		A	11000	11000
24962	18	36	113	1.0	0.50	11	8	2.20	11	3	SOIL		A	11000	11050
24961	13	27	103	0.3	0.47	11	6	2.09	12	4	SOIL		A	11000	11100
24960	16	31	123	1.1	0.47	14	8	2.51	12	1	SOIL		A	11000	11150
24959	12	19	93	0.1	0.39	10	7	2.04	18	1	SOIL		A	11000	11200
24958	15	30	113	0.5	0.47	11	9	2.51	13	4	SOIL		A	11000	11250
24957	25	28	184	1.3	0.81	12	8	2.83	14	2	SOIL		A	11000	11300
24956	21	27	146	0.7	0.38	15	9	3.08	16	1	SOIL	11400 NO SAMPLE - SWAMP	A	11000	11350
24954	19	39	178	0.7	1.02	14	7	2.55	16	3	SOIL	EOL	A	11000	11500
23093	23	123	151	3.8	0.11	6	3	1.80	44	15	SOIL	RESAMPLE	A	11500	10300
23095	14	153	182	1.8	0.16	4	2	1.42	56	16	SOIL	RESAMPLE	A	11500	10350
23096	32	93	201	3.2	0.13	7	7	2.59	46	14	SOIL	RESAMPLE	A	11500	10400
23097	20	73	231	2.0	0.18	8	5	2.45	25	10	SOIL	RESAMPLE	A	11500	10450
23099	26	97	385	4.5	0.34	10	5	2.28	31	6	SOIL	RESAMPLE	A	11500	10550
23100	26	57	202	1.7	0.65	9	7	2.77	23	8	SOIL		A	12000	11400
22634	42	53	296	5.3	1.12	16	11	4.10	28	8	SOIL		A	12200	11450
22636	322	48	172	0.3	1.34	23	24	5.19	2	5	GRAB	AUG, BASALT, W/EP-PY	A		
22637	2	8	126	0.1	0.46	4	4	1.99	5	3	GRAB	VOLCANIC BX W/TRACE OF PY	B	9780	10500
27981	7	17	65	0.4	0.28	9	5	2.02	5	3	SOIL		B	9400	9500
27980	7	24	62	0.2	0.14	9	6	2.21	3	2	SOIL		B	9400	9550
27979	8	15	78	0.1	0.12	12	6	3.00	9	3	SOIL		B	9400	9600
27978	8	15	71	0.2	0.15	9	7	4.17	10	10	SOIL		B	9400	9650
27977	8	19	55	0.2	0.15	9	6	3.88	6	1	SOIL		B	9400	9700

Sample	Cu (ppm)	Pb (ppm)	Zn (ppm)	Ag (ppm)	Ca (%)	Ni (ppm)	Co (ppm)	Fe (%)	As (ppm)	Au (ppb)	Sample Type	Remarks	Grid	North	East
29394	13	12	52	0.1	0.14	7	5	2.00	2	1	SOIL		B	10500	9950
29395	11	16	39	0.1	0.12	5	3	1.46	2	1	SOIL		B	10500	10000
29396	12	12	69	0.2	0.19	8	7	2.34	2	1	SOIL		B	10500	10050
29397	12	21	84	0.1	0.24	12	6	2.20	2	2	SOIL		B	10500	10100
29398	14	20	364	0.1	0.32	10	6	2.12	2	1	SOIL		B	10500	10150
29399	3	35	59	0.1	0.16	4	2	1.20	2	1	SOIL		B	10500	10200
29400	12	29	202	0.2	0.16	10	6	2.46	2	1	SOIL		B	10500	10250
29401	13	25	83	0.2	0.14	6	6	3.03	6	2	SOIL		B	10500	10300
29402	11	34	86	1.1	0.12	7	4	1.79	3	1	SOIL		B	10500	10350
29403	12	97	89	0.4	0.21	6	4	1.82	2	3	SOIL		B	10500	10400
29404	23	50	80	0.8	0.14	5	4	1.81	2	2	SOIL		B	10500	10450
29405	10	32	57	0.6	0.20	7	3	1.50	2	2	SOIL		B	10500	10500
24923	10	50	62	0.3	0.07	4	3	2.24	19	720	SOIL		B	11100	10000
24924	11	43	53	0.5	0.07	4	3	3.61	27	15	SOIL		B	11100	10050
24925	10	59	69	1.0	0.14	4	3	2.68	25	6	SOIL		B	11100	10100
24926	9	59	101	0.8	0.12	5	3	2.24	22	8	SOIL		B	11100	10150
24927	8	55	54	0.1	0.06	3	3	2.05	25	7	SOIL		B	11100	10200
24928	7	53	97	0.7	0.18	5	3	1.36	9	2	SOIL		B	11100	10250
24929	8	45	97	2.5	0.14	6	4	1.76	10	8	SOIL		B	11100	10300
24930	27	38	146	13.3	0.80	9	6	2.52	22	5	SOIL		B	11100	10350
24931	22	58	191	3.0	0.20	10	8	2.80	22	12	SOIL		B	11100	10400
24932	7	36	68	0.2	0.09	4	3	1.50	11	9	SOIL		B	11100	10450
24933	7	42	84	1.0	0.12	6	3	1.80	12	15	SOIL		B	11100	10500
24934	11	44	100	2.0	0.11	8	4	1.96	15	42	SOIL		B	11100	10550
24935	17	36	127	0.6	0.11	12	7	2.84	15	1	SOIL		B	11100	10600
24936	24	58	150	1.1	0.13	10	7	2.67	34	68	SOIL		B	11100	10650
24937	13	46	113	1.4	0.16	7	5	2.85	25	20	SOIL	NEXT TO CREEK	B	11100	10700
24938	14	39	102	0.9	0.30	7	5	2.08	16	2	SOIL	NEXT TO CREEK	B	11100	10750
24939	17	36	75	0.1	0.08	6	4	3.85	21	8	SOIL		B	11100	10800
24940	24	57	182	2.9	1.62	11	14	3.10	19	2	SOIL		B	11100	10850
24941	27	79	197	4.0	0.64	15	22	3.65	26	2	SOIL		B	11100	10900
24942	19	47	129	2.7	0.66	10	7	2.20	10	18	SOIL		B	11100	10950
24943	10	34	57	0.5	0.12	5	3	1.26	7	80	SOIL		B	11100	11000
24944	12	38	80	1.7	0.34	8	5	1.55	6	7	SOIL		B	11100	11050
24945	15	32	114	0.6	0.57	11	6	2.24	15	9	SOIL		B	11100	11100
24946	33	49	229	1.8	0.74	20	11	3.89	28	8	SOIL		B	11100	11150
24947	12	28	106	0.3	0.49	10	6	1.90	12	25	SOIL		B	11100	11200
24948	19	26	225	0.7	0.64	13	7	2.68	15	2	SOIL		B	11100	11250
24949	18	27	136	0.6	0.72	14	8	2.40	15	4	SOIL		B	11100	11300
24950	22	29	157	0.8	0.78	14	15	2.99	15	2	SOIL		B	11100	11350
24951	20	30	117	0.4	0.38	14	8	2.82	17	5	SOIL		B	11100	11400
24952	14	49	80	0.3	0.23	6	3	1.82	12	2	SOIL		B	11100	11450
24953	25	75	174	0.4	0.41	10	8	2.77	37	1	SOIL	EOL	B	11100	11500

GEOCHEMICAL ANALYSIS CERTIFICATE

Fox Geological Consultants PROJECT 138F

File # 90-3129

Page 1

1409 - 409 Granville St., Vancouver BC V6C 1T2

Submitted by: G. GOODALL

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
22368	1	20	11	67	.3	15	13	936	4.13	26	5	ND	2	106	.2	2	2	91	.89	.073	3	25	.67	114	.14	3	2.75	.09	.12	1	1
22634	2	42	53	296	5.3	16	11	1271	4.10	28	5	ND	1	62	1.4	2	2	58	1.12	.093	12	21	.73	218	.08	2	3.45	.02	.14	1	8
22635	1	16	41	159	.6	12	8	467	3.23	15	5	ND	2	18	.4	2	2	57	.22	.032	7	22	.60	139	.10	2	1.92	.01	.05	1	3
23093	2	23	123	151	3.8	6	3	341	1.80	44	5	ND	3	11	.3	2	2	29	.11	.032	9	10	.41	58	.08	2	1.72	.01	.06	1	15
23095	2	14	153	182	1.8	4	2	389	1.42	56	5	ND	3	12	.2	2	2	22	.16	.030	11	10	.29	50	.08	2	.93	.01	.04	1	16
23096	3	32	93	201	3.2	7	7	614	2.59	46	5	ND	2	16	.2	2	2	36	.13	.040	11	13	.48	79	.08	3	2.19	.01	.09	1	14
23097	2	20	73	231	2.0	8	5	458	2.45	25	5	ND	2	17	.2	2	2	36	.18	.039	7	13	.61	92	.10	2	2.04	.01	.12	1	10
23099	3	26	97	385	4.5	10	5	638	2.28	31	5	ND	1	31	.7	6	2	42	.34	.052	11	16	.58	117	.07	2	2.30	.02	.08	1	6
23100	1	26	57	202	1.7	9	7	822	2.77	23	5	ND	1	38	1.1	3	2	53	.65	.058	9	16	.70	123	.10	3	1.86	.01	.08	1	8
24736	4	43	68	137	.9	8	3	850	9.02	16	5	ND	1	105	.9	10	5	110	.08	.156	7	16	1.16	200	.08	4	2.82	.06	.30	1	1
24737	4	80	60	92	1.4	6	3	612	8.14	14	5	ND	1	86	.6	6	2	76	.03	.213	10	11	.88	137	.04	3	2.24	.05	.13	1	1
24738	4	121	17	51	.6	5	3	308	3.99	6	5	ND	1	34	.2	2	2	58	.06	.096	14	13	.65	90	.09	2	2.22	.02	.14	3	2
24739	1	23	15	52	.4	10	6	196	4.11	18	5	ND	1	18	.2	10	2	90	.12	.069	5	28	.43	60	.14	4	2.93	.01	.05	1	2
24740	1	14	17	54	.1	10	5	205	3.12	13	5	ND	1	23	.2	3	2	63	.16	.062	6	24	.37	73	.12	2	1.84	.01	.05	1	1
24741	1	9	22	101	.4	13	7	254	1.68	8	5	ND	1	61	.9	4	2	36	.70	.098	3	22	.55	88	.05	2	2.02	.02	.05	1	1
24742	1	14	13	122	.1	14	7	401	2.73	13	5	ND	1	51	.2	5	2	57	.43	.061	5	23	.61	75	.13	2	1.69	.02	.07	1	1
24743	2	21	11	149	.5	16	9	809	3.59	12	5	ND	1	50	.6	7	2	86	.47	.148	6	26	.77	65	.05	3	2.39	.02	.07	1	1
24744	1	16	12	45	.1	11	5	203	3.76	14	5	ND	1	20	.2	2	2	78	.13	.059	4	30	.37	67	.12	2	2.24	.01	.04	2	1
24745	1	16	15	56	.5	12	7	243	3.48	13	5	ND	1	35	.5	6	2	87	.31	.071	3	27	.62	51	.14	4	2.50	.02	.07	1	1
24746	1	25	22	106	.1	22	10	533	3.12	23	5	ND	3	55	.4	5	3	66	.30	.039	10	28	.61	103	.17	2	2.35	.01	.18	1	2
24747	1	17	16	87	.1	14	8	302	2.24	9	5	ND	1	58	.4	3	2	60	.42	.058	8	25	.54	73	.16	3	1.60	.03	.08	1	1
24748	1	27	38	189	1.1	26	13	710	3.21	25	5	ND	1	72	1.0	7	2	69	.52	.069	7	34	.78	183	.10	2	3.82	.03	.15	1	2
24749	1	18	24	235	1.1	17	8	441	2.71	12	5	ND	1	57	.9	3	2	54	.83	.080	6	23	.60	135	.08	2	2.82	.01	.09	1	1
24750	1	35	9	89	.2	28	15	524	3.59	9	5	ND	1	54	.4	7	2	95	.43	.102	6	44	1.01	87	.12	2	2.74	.04	.08	1	2
24923	2	10	50	62	.3	4	3	186	2.24	19	5	ND	1	10	.2	3	2	49	.07	.036	7	12	.24	38	.09	2	1.28	.01	.02	1	720
24924	2	11	43	53	.5	4	3	235	3.61	27	5	ND	1	10	.2	2	2	79	.07	.041	6	12	.14	26	.12	2	1.01	.01	.01	2	15
24925	2	10	59	69	1.0	4	3	176	2.68	25	5	ND	1	14	.6	3	2	47	.14	.035	5	17	.24	38	.06	2	1.63	.01	.01	1	6
24926	1	9	59	101	.8	5	3	293	2.24	22	5	ND	1	12	.3	2	2	46	.12	.032	8	14	.34	43	.10	2	1.16	.01	.01	1	8
24927	1	8	55	54	.1	3	3	229	2.05	25	5	ND	1	8	.2	2	3	49	.06	.033	7	11	.23	22	.09	2	.74	.01	.01	1	7
24928	1	7	53	97	.7	5	3	296	1.36	9	5	ND	1	20	.5	2	2	26	.18	.047	8	10	.30	73	.04	2	1.11	.01	.02	1	2
24929	1	8	45	97	2.5	6	4	302	1.76	10	5	ND	1	13	.4	2	2	33	.14	.029	6	12	.47	41	.11	2	1.29	.01	.01	1	8
24930	1	27	38	146	13.3	9	6	938	2.52	22	5	ND	1	57	1.3	3	2	37	.80	.320	15	18	.35	179	.01	2	2.36	.01	.04	1	5
24931	1	22	58	191	3.0	10	8	678	2.80	22	5	ND	1	19	.6	3	4	47	.20	.073	9	18	.54	118	.06	2	2.52	.01	.06	1	12
24932	1	7	36	68	.2	4	3	244	1.50	11	5	ND	1	11	.2	2	2	31	.09	.018	5	10	.39	40	.09	2	.95	.01	.01	1	9
24933	1	7	42	84	1.0	6	3	267	1.80	12	5	ND	1	12	.2	2	2	32	.12	.031	8	13	.42	42	.09	2	1.28	.01	.02	1	15
24934	1	11	44	100	2.0	8	4	328	1.96	15	5	ND	1	12	.2	2	2	37	.11	.029	6	15	.52	58	.09	2	1.48	.01	.04	1	42
STANDARD C/AU-S	18	58	37	131	6.7	70	32	1042	3.94	41	22	8	38	53	18.0	15	18	55	.51	.089	35	56	.90	182	.09	33	1.89	.06	.14	12	53

ICP - .500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER. THIS LEACH IS PARTIAL FOR MN FE SR CA P LA CR MG BA TI B W AND LIMITED FOR NA K AND AL. AU DETECTION LIMIT BY ICP IS 3 PPM. - SAMPLE TYPE: P1-P12 Soil P13 Rock AU* ANALYSIS BY ACID LEACH/AA FROM 10 GM SAMPLE

DATE RECEIVED: AUG 3 1990

DATE REPORT MAILED:

Aug 9/90

SIGNED BY: *C. Leung* D. TOYE, C. LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	M ppm	Au* ppb
24935	1	17	36	127	.6	12	7	511	2.84	15	5	ND	1	14	.3	2	2	67	.11	.034	4	20	.76	60	.12	2	1.87	.01	.07	1	1
24936	1	24	58	150	1.1	10	7	321	2.67	34	5	ND	1	13	.4	2	5	43	.13	.055	7	15	.48	57	.08	2	1.91	.01	.03	1	68
24937	1	13	46	113	1.4	7	5	314	2.85	25	5	ND	1	14	.4	2	2	44	.16	.068	6	15	.40	42	.06	2	1.82	.01	.04	1	20
24938	1	14	39	102	.9	7	5	365	2.08	16	5	ND	1	19	.2	2	3	39	.30	.062	7	14	.44	55	.07	2	1.27	.01	.04	1	2
24939	1	17	36	75	.1	6	4	235	3.85	21	5	ND	1	9	.2	3	2	87	.08	.051	6	16	.29	37	.15	2	1.09	.01	.03	1	8
24940	2	24	57	182	2.9	11	14	3982	3.10	19	6	ND	1	75	3.0	3	2	56	1.62	.160	7	17	.62	133	.03	3	2.43	.01	.08	1	2
24941	3	27	79	197	4.0	15	22	2123	3.65	26	5	ND	1	61	1.3	2	2	76	.64	.110	10	24	.53	181	.04	2	3.32	.01	.12	1	2
24942	2	19	47	129	2.7	10	7	565	2.20	10	5	ND	1	56	.8	2	2	46	.66	.125	9	17	.50	103	.03	2	2.15	.01	.07	1	18
24943	1	10	34	57	.5	5	3	206	1.26	7	5	ND	1	12	.2	2	2	30	.12	.021	6	11	.35	32	.10	2	1.03	.01	.03	1	80
24944	1	12	38	80	1.7	8	5	298	1.55	6	5	ND	1	33	.4	2	2	34	.34	.057	6	18	.40	74	.07	2	1.45	.01	.06	1	7
24945	2	15	32	114	.6	11	6	445	2.24	15	5	ND	1	47	.2	2	3	47	.57	.072	6	18	.51	81	.09	2	1.59	.02	.07	1	9
24946	7	33	49	229	1.8	20	11	903	3.89	28	5	ND	1	70	.9	2	2	72	.74	.108	13	29	.69	168	.08	2	3.61	.02	.14	1	8
24947	2	12	28	106	.3	10	6	360	1.90	12	5	ND	1	50	.2	2	2	38	.49	.079	9	17	.51	86	.07	2	1.82	.02	.06	1	25
24948	1	19	26	225	.7	13	7	800	2.68	15	5	ND	1	55	1.0	2	2	49	.64	.105	9	19	.61	189	.06	2	2.43	.02	.07	1	2
24949	1	18	27	136	.6	14	8	616	2.40	15	5	ND	1	67	.4	3	2	45	.72	.088	7	18	.61	148	.06	2	2.26	.02	.09	1	4
24950	1	22	29	157	.8	14	15	1309	2.99	15	5	ND	1	73	.5	2	2	53	.78	.097	8	17	.62	176	.05	2	2.68	.02	.10	1	2
24951	1	20	30	117	.4	14	8	511	2.82	17	5	ND	1	37	.2	3	3	54	.38	.052	8	20	.65	99	.13	2	2.03	.02	.09	1	5
24952	1	14	49	80	.3	6	3	185	1.82	12	5	ND	1	27	.4	2	2	38	.23	.056	9	15	.28	84	.06	2	1.49	.01	.04	1	2
24953	1	25	75	174	.4	10	8	747	2.77	37	5	ND	1	38	.8	3	2	49	.41	.060	9	18	.66	83	.09	3	1.62	.01	.07	1	1
24954	1	19	39	178	.7	14	7	824	2.55	16	5	ND	1	71	.7	2	2	47	1.02	.084	8	24	.64	195	.06	2	2.40	.02	.09	1	3
24955	1	19	38	170	.4	13	8	529	2.75	17	5	ND	1	56	.4	2	2	53	.81	.066	8	23	.68	154	.08	2	2.33	.02	.09	1	7
24956	1	21	27	146	.7	15	9	663	3.08	16	5	ND	1	39	.2	2	2	59	.38	.070	8	23	.76	132	.10	2	2.60	.02	.09	1	1
24957	1	25	28	184	1.3	12	8	851	2.83	14	5	ND	1	72	1.0	2	2	53	.81	.146	10	18	.62	177	.04	4	2.59	.02	.08	1	2
24958	2	15	30	113	.5	11	9	681	2.51	13	5	ND	1	57	.5	3	2	50	.47	.057	8	19	.59	93	.12	2	1.72	.04	.08	1	4
24959	2	12	19	93	.1	10	7	277	2.04	18	5	ND	1	47	.2	2	2	40	.39	.067	5	16	.56	85	.08	2	1.75	.05	.04	1	1
24960	1	16	31	123	1.1	14	8	334	2.51	12	5	ND	1	49	.3	2	2	53	.47	.056	5	20	.68	83	.13	3	2.34	.03	.06	1	1
24961	1	13	27	103	.3	11	6	344	2.09	12	5	ND	1	49	.3	3	2	44	.47	.068	7	19	.50	87	.09	3	1.64	.03	.06	1	4
24962	1	18	36	113	1.0	11	8	632	2.20	11	5	ND	1	51	.6	2	2	48	.50	.074	6	17	.52	95	.07	2	1.83	.02	.07	1	3
24963	1	11	24	74	.6	9	5	301	1.85	10	5	ND	1	26	.2	2	2	38	.26	.039	7	15	.48	51	.11	2	1.38	.01	.06	1	6
24964	2	14	33	108	1.3	10	7	501	2.16	12	5	ND	1	32	.5	2	2	44	.34	.052	9	17	.53	73	.09	3	1.64	.02	.05	1	18
24965	1	21	36	140	2.5	14	14	919	2.62	12	5	ND	1	47	.7	2	2	55	.53	.103	9	20	.86	103	.05	2	2.65	.02	.09	1	2
24966	1	16	46	143	2.8	10	7	652	2.05	14	5	ND	1	46	1.0	2	2	36	.72	.085	7	15	.47	129	.06	3	2.08	.02	.08	1	18
24967	1	16	48	110	2.6	8	6	392	1.87	9	5	ND	1	30	.3	2	2	36	.45	.042	8	14	.49	75	.10	2	1.53	.01	.06	1	4
24968	1	24	48	210	4.2	13	15	2083	3.60	20	5	ND	1	65	1.4	2	2	64	1.17	.194	6	20	.76	202	.03	3	3.21	.02	.14	1	6
24969	1	14	67	119	1.6	6	4	271	2.30	20	5	ND	1	11	.3	2	2	36	.13	.053	8	15	.41	52	.06	2	2.39	.01	.04	1	107
24970	1	19	33	89	.7	11	7	333	2.58	19	5	ND	1	19	.5	2	2	43	.18	.038	9	18	.52	60	.10	3	1.48	.01	.04	1	26
STANDARD C/AU-S	18	58	41	131	6.9	70	32	1044	3.95	42	20	7	38	53	18.4	16	19	56	.51	.093	39	55	.91	182	.09	34	1.88	.06	.14	13	51

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Tl %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
24971	1	3	40	50	.5	4	2	177	1.10	3	5	ND	1	15	.2	2	2	28	.13	.021	4	7	.21	47	.10	2	.80	.01	.03	1	11
24972	1	7	40	36	1.0	4	3	144	2.27	10	5	ND	1	8	.2	2	2	44	.07	.034	6	9	.18	42	.06	2	1.23	.01	.01	1	8
24973	1	7	51	86	.7	5	3	269	1.58	6	5	ND	1	11	.2	2	2	37	.09	.024	5	11	.44	48	.09	2	1.44	.01	.02	1	8
24974	1	12	48	82	.7	5	4	244	2.80	19	5	ND	1	10	.3	2	3	45	.09	.051	6	12	.39	46	.06	2	1.81	.01	.03	1	15
24975	1	13	64	102	1.0	5	3	286	1.97	21	5	ND	1	16	.2	2	2	36	.11	.034	5	10	.41	62	.07	2	1.43	.01	.02	1	8
24976	1	12	48	63	1.4	4	4	542	2.70	19	5	ND	1	18	.2	2	2	48	.22	.055	3	10	.17	43	.05	2	1.07	.01	.03	1	5
24977	2	23	35	188	3.7	8	9	2295	2.64	25	5	ND	1	86	4.3	3	2	38	1.21	.203	20	11	.33	258	.01	2	2.20	.01	.05	1	18
24978	1	12	46	74	.8	5	4	227	1.81	10	5	ND	1	11	.3	2	2	38	.11	.025	8	11	.40	50	.07	2	1.63	.01	.01	1	15
24979	1	9	43	53	.9	5	3	217	1.99	8	5	ND	1	10	.2	2	2	46	.09	.031	7	12	.22	34	.12	2	1.09	.01	.02	1	11
24980	1	6	45	60	.4	4	3	216	1.79	9	5	ND	1	10	.2	2	2	40	.10	.028	7	10	.32	35	.10	2	1.23	.01	.02	1	10
24981	1	10	65	72	1.9	3	3	225	2.30	28	5	ND	1	8	.2	2	2	47	.07	.032	7	9	.25	27	.09	2	1.06	.01	.01	1	19
24982	2	13	54	62	.5	4	3	286	3.34	33	5	ND	1	11	.2	2	3	60	.09	.043	3	12	.22	24	.07	2	1.21	.01	.02	1	11
24983	1	5	32	27	.8	2	1	107	1.10	2	5	ND	1	11	.2	2	2	34	.09	.022	5	7	.04	31	.11	2	.88	.01	.01	1	4
24984	1	11	32	67	.5	5	5	291	3.60	16	5	ND	1	10	.2	2	5	68	.13	.058	5	13	.28	36	.09	2	1.47	.01	.02	1	66
24985	1	8	26	72	.2	5	4	203	2.58	10	5	ND	1	10	.2	3	2	44	.12	.048	5	11	.38	41	.06	2	2.38	.01	.01	1	5
24986	1	20	41	97	1.5	7	6	314	2.85	22	5	ND	1	11	.2	4	2	39	.14	.071	6	12	.51	48	.05	2	2.20	.01	.02	2	15
24987	1	12	49	141	1.1	6	12	3097	2.20	9	5	ND	1	25	1.2	2	2	35	.32	.071	6	11	.48	117	.03	2	1.48	.01	.04	1	17
24988	2	21	55	230	6.8	13	6	441	3.11	19	5	ND	1	28	.7	6	2	45	.23	.135	6	17	.67	179	.02	2	3.92	.01	.10	1	9
24989	1	12	52	81	1.4	7	4	281	2.26	15	5	ND	1	13	.2	2	2	50	.12	.037	6	14	.48	59	.11	2	1.47	.01	.04	1	8
24990	1	10	49	87	.8	5	3	234	2.49	16	5	ND	1	9	.2	4	2	39	.08	.040	5	12	.38	40	.07	2	1.66	.01	.02	1	10
24991	1	10	50	85	.4	5	4	254	2.34	20	5	ND	1	10	.2	2	2	47	.08	.036	6	13	.38	37	.09	2	1.51	.01	.02	1	28
24992	1	15	55	94	1.4	6	4	246	2.71	29	5	ND	1	11	.3	4	2	45	.11	.060	5	16	.38	47	.08	2	2.64	.01	.02	1	12
24993	1	15	79	197	2.0	7	4	293	2.64	26	5	ND	1	12	.3	3	2	43	.12	.052	5	15	.33	35	.08	2	1.76	.01	.04	1	14
24994	1	16	93	145	.6	6	4	596	2.52	41	5	ND	1	16	.3	2	3	47	.19	.064	5	13	.27	71	.05	2	1.25	.01	.04	1	26
24995	1	17	47	103	.2	8	6	458	2.83	13	5	ND	1	16	.4	2	2	48	.18	.050	6	16	.45	69	.09	2	1.49	.01	.05	1	10
24996	1	28	45	156	6.1	12	9	717	2.77	13	5	ND	1	56	.9	3	2	54	.83	.152	8	19	.69	160	.05	2	2.78	.03	.08	1	16
24997	1	38	48	144	5.2	10	8	1704	2.81	15	5	ND	1	61	2.9	5	2	67	1.19	.172	7	21	.51	104	.03	2	2.70	.02	.03	1	4
24998	1	9	37	120	.3	9	6	445	2.12	6	5	ND	1	20	.2	2	2	45	.36	.028	3	14	.58	56	.11	2	1.32	.02	.03	1	1
24999	1	14	37	135	.9	11	7	393	2.45	6	5	ND	1	28	.2	2	2	51	.29	.048	7	16	.73	70	.09	2	1.88	.01	.06	1	6
25000	1	9	35	105	1.0	11	6	326	2.15	4	5	ND	1	26	.2	2	2	44	.25	.035	4	20	.61	70	.10	2	1.59	.01	.03	1	10
26098	1	32	26	196	.4	13	7	678	2.79	6	5	ND	1	22	.7	4	2	56	.33	.056	12	21	.60	410	.07	2	2.56	.01	.05	1	6
26099	1	9	20	47	.1	10	4	219	3.22	8	5	ND	2	13	.2	2	2	61	.10	.059	4	22	.34	54	.12	2	2.02	.01	.03	1	1
26100	1	14	17	66	.1	10	5	261	3.85	10	5	ND	1	14	.2	2	4	69	.12	.079	6	23	.38	55	.11	2	2.33	.01	.02	1	7
26101	1	11	21	64	.1	9	4	184	3.28	13	5	ND	1	9	.2	4	2	63	.08	.085	4	24	.33	41	.12	2	3.52	.01	.03	1	1
26102	1	11	16	58	.2	9	4	204	3.23	9	5	ND	1	10	.2	2	2	56	.10	.089	6	21	.33	48	.09	2	3.32	.01	.03	1	3
26103	1	8	19	55	.1	8	4	195	2.77	6	5	ND	1	10	.2	2	4	52	.09	.063	6	20	.36	41	.10	2	2.65	.01	.03	1	7
STANDARD C/AU-S	18	59	38	131	7.0	73	31	1044	3.95	43	21	7	39	52	18.7	15	19	56	.51	.093	37	57	.91	182	.09	35	1.89	.06	.14	11	50

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Hg %	Ba ppm	Tl %	B ppm	Al %	Na %	K %	M ppm	Au* ppb
26104	1	9	17	50	.1	10	4	222	2.80	9	5	ND	1	13	.2	2	2	49	.14	.073	5	24	.32	43	.10	3	2.56	.01	.02	2	2
26105	1	15	29	70	.4	11	5	253	3.21	16	5	ND	1	10	.2	6	2	57	.10	.081	7	25	.38	39	.10	3	2.80	.01	.03	1	3
26106	1	12	28	63	.2	11	5	281	3.02	9	5	ND	1	12	.2	2	2	54	.12	.057	9	20	.46	55	.10	3	2.28	.01	.04	1	27
26107	1	34	28	308	.2	10	6	284	2.34	9	5	ND	1	13	.9	4	2	51	.13	.043	7	20	.63	51	.09	3	2.31	.01	.04	1	275
26108	1	21	63	142	.3	9	4	246	2.77	9	5	ND	1	10	.2	3	2	55	.09	.065	6	21	.39	45	.09	3	2.62	.01	.03	1	13
26109	1	15	31	100	.1	13	6	291	2.54	8	5	ND	1	11	.2	4	2	51	.09	.040	7	19	.52	70	.10	3	2.53	.01	.05	1	2
26110	1	16	33	98	.6	11	5	258	3.24	10	5	ND	1	11	.2	2	2	56	.12	.104	7	23	.44	56	.09	3	3.60	.01	.04	1	1
26111	1	16	29	107	.1	11	7	470	2.81	8	5	ND	1	14	.2	2	2	56	.15	.087	7	19	.65	60	.05	3	2.01	.01	.08	1	4
26112	1	13	55	100	.1	10	5	260	1.77	4	5	ND	1	12	.2	2	2	39	.14	.032	6	15	.46	57	.10	3	1.32	.01	.04	1	2
26113	1	10	23	94	.1	9	6	325	2.09	3	5	ND	1	17	.3	2	2	49	.20	.050	6	16	.55	73	.07	2	1.35	.01	.04	1	4
26114	1	11	40	87	.2	7	4	250	2.42	6	5	ND	1	11	.2	2	2	42	.14	.069	6	16	.33	58	.08	2	1.98	.01	.03	1	2
26115	1	10	45	123	.2	7	4	345	2.72	9	5	ND	1	14	.2	4	2	47	.13	.079	6	17	.39	49	.09	3	2.35	.01	.02	1	1
26116	1	11	27	60	.2	7	4	234	2.93	5	5	ND	1	13	.2	2	2	48	.11	.077	6	18	.31	43	.09	2	1.63	.01	.02	1	1
26117	1	17	38	104	.1	11	7	390	3.34	11	5	ND	1	15	.2	4	2	59	.15	.078	8	20	.52	45	.11	3	2.60	.01	.02	1	2
26118	1	13	25	107	.3	10	6	571	3.48	5	5	ND	1	18	.2	2	2	56	.15	.083	6	19	.38	68	.10	2	1.81	.01	.03	1	2
26119	1	9	23	110	.2	7	4	341	3.15	7	5	ND	1	20	.3	4	2	56	.20	.066	8	16	.36	70	.08	3	1.40	.01	.03	1	2
26120	1	12	20	111	.1	8	5	417	2.80	7	5	ND	1	20	.2	2	2	46	.21	.089	6	18	.45	89	.07	2	1.81	.01	.03	1	3
26121	1	14	44	358	.1	10	6	354	3.08	9	5	ND	1	16	1.0	3	2	52	.15	.113	7	21	.47	60	.13	4	2.36	.01	.03	1	3
26122	1	17	21	117	.1	13	6	467	3.00	10	5	ND	1	15	.2	5	2	54	.14	.116	8	22	.54	56	.11	3	2.48	.01	.03	1	1
26123	1	8	16	84	.1	9	5	501	2.64	4	5	ND	1	21	.2	2	2	45	.27	.063	5	17	.36	57	.06	2	1.28	.01	.03	1	1
26124	1	12	20	83	.1	12	6	288	3.45	10	5	ND	1	16	.2	5	2	68	.18	.061	6	25	.39	56	.15	2	1.70	.01	.02	1	2
26125	1	19	48	205	.1	11	6	454	2.45	9	5	ND	1	22	.2	2	2	45	.28	.061	8	17	.54	109	.05	3	1.84	.01	.03	1	3
26126	1	13	25	103	.1	10	5	305	2.71	9	5	ND	1	18	.2	2	2	47	.19	.055	7	17	.44	72	.09	3	1.97	.01	.04	1	4
26127	1	11	21	79	.1	10	5	242	3.16	12	5	ND	1	14	.2	2	2	55	.10	.069	6	19	.42	45	.10	2	2.20	.01	.04	1	2
26128	1	17	18	112	.2	15	7	281	3.19	15	5	ND	1	19	.2	4	2	63	.19	.046	7	22	.59	83	.09	3	2.30	.01	.05	1	1
26129	1	15	43	102	.1	12	6	285	3.55	11	5	ND	1	16	.2	2	2	62	.15	.064	6	20	.47	64	.09	2	2.38	.01	.05	1	5
26130	1	15	20	95	.1	15	6	283	3.18	16	5	ND	1	18	.2	5	2	57	.11	.080	8	24	.55	62	.12	2	3.03	.01	.05	1	4
26131	1	11	22	79	.2	11	5	238	2.90	11	5	ND	1	16	.2	3	2	61	.14	.049	6	20	.46	64	.12	4	2.17	.01	.04	1	4
26132	1	19	21	83	.3	13	6	315	2.82	9	5	ND	1	15	.2	2	2	62	.13	.037	9	21	.61	64	.14	5	1.94	.01	.04	1	3
26133	1	12	22	56	.2	11	5	216	2.40	8	5	ND	1	12	.2	2	2	50	.11	.042	7	19	.47	51	.12	2	2.05	.01	.03	1	2
26134	1	12	13	64	.1	11	5	214	3.35	14	5	ND	2	17	.2	3	3	62	.16	.060	6	23	.37	50	.12	3	2.38	.01	.03	1	2
26135	1	11	19	54	.1	8	4	188	3.27	18	5	ND	1	17	.2	6	2	69	.16	.060	6	22	.29	34	.10	2	2.33	.01	.02	1	1
26136	1	11	17	50	.1	8	4	192	2.50	12	5	ND	1	14	.2	2	2	51	.13	.051	8	18	.31	47	.09	4	1.64	.01	.03	1	1
26137	1	19	20	352	.3	12	6	314	2.29	5	5	ND	1	20	.5	2	2	46	.20	.039	7	16	.57	70	.08	2	2.04	.01	.04	1	1
26138	1	15	14	82	.2	13	5	237	3.07	15	5	ND	1	16	.2	2	2	62	.14	.054	7	22	.45	66	.11	5	2.38	.01	.05	1	6
26139	1	8	13	65	.3	11	5	262	2.13	6	5	ND	1	27	.2	2	2	46	.30	.043	6	17	.55	81	.12	2	1.49	.01	.03	1	3
STANDARD C/AU-S	19	58	39	131	7.0	72	31	1045	3.95	40	23	8	38	52	19.0	16	21	60	.51	.093	36	56	.91	182	.09	37	1.91	.06	.14	13	52

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
26140	1	7	14	60	.3	9	5	312	2.69	8	5	ND	1	18	.2	2	2	49	.18	.028	5	19	.41	45	.11	3	1.14	.01	.07	1	1
26141	1	65	30	368	.5	23	13	1513	3.84	14	5	ND	1	69	2.9	2	2	56	.83	.117	15	29	.75	219	.05	2	4.22	.02	.18	1	1
26142	1	10	16	89	.4	12	6	270	2.63	6	5	ND	1	17	.2	2	2	49	.15	.038	6	20	.52	75	.10	3	2.06	.01	.06	1	264
26143	1	7	19	69	.3	10	5	249	2.13	4	5	ND	2	13	.2	2	2	46	.12	.022	5	17	.43	43	.12	3	1.56	.01	.05	1	13
26144	1	13	18	99	.2	13	7	311	2.60	5	5	ND	1	22	.2	2	2	51	.30	.039	7	19	.64	108	.09	4	2.28	.02	.05	1	3
26145	1	21	14	132	.2	14	9	522	2.85	7	5	ND	1	19	.4	2	2	54	.24	.040	7	23	.78	172	.09	2	2.45	.01	.06	1	3
26146	1	10	21	101	.1	12	6	291	2.38	5	5	ND	1	21	.3	2	2	51	.23	.034	6	20	.66	119	.11	3	1.81	.01	.05	1	216
26147	1	10	27	459	.4	14	8	389	3.00	4	5	ND	1	17	.6	2	2	51	.25	.052	9	20	.58	148	.11	4	2.46	.01	.05	1	9
26148	1	79	442	5802	.2	15	8	603	2.89	12	5	ND	1	26	11.4	2	2	53	.45	.086	9	20	.67	91	.09	2	1.96	.02	.05	1	1
26149	1	15	123	310	.5	10	6	354	3.26	8	5	ND	3	10	.3	2	3	50	.09	.055	5	21	.47	43	.11	3	3.28	.01	.03	2	2
26150	1	11	39	100	.6	10	6	285	3.19	7	5	ND	1	12	.2	2	2	49	.13	.068	4	18	.46	56	.09	2	2.76	.01	.04	1	4
27896	1	11	29	108	.9	10	5	292	2.16	7	5	ND	1	30	.4	2	2	40	.28	.061	6	18	.48	79	.07	3	1.66	.01	.05	1	6
27897	1	12	25	147	1.0	13	7	503	2.57	8	5	ND	1	50	.2	2	2	47	.50	.065	6	23	.52	121	.09	2	2.06	.02	.10	1	3
27898	1	14	31	149	1.3	14	7	367	2.28	5	5	ND	1	57	.5	2	2	42	.55	.057	5	21	.58	127	.06	2	2.54	.02	.10	1	2
27899	1	14	27	143	1.0	13	8	564	2.50	13	5	ND	1	70	.7	2	2	50	.71	.084	6	21	.61	142	.08	3	2.30	.04	.08	1	4
27900	1	12	22	108	.8	13	7	336	2.18	5	5	ND	2	46	.5	3	2	43	.39	.050	6	19	.59	113	.10	4	1.97	.03	.06	1	11
27901	1	14	28	152	.4	15	10	831	2.95	6	5	ND	1	73	.5	2	2	58	.62	.070	6	22	.73	121	.09	3	2.68	.04	.10	1	1
27902	1	6	23	49	.1	7	4	212	3.49	5	5	ND	1	11	.2	2	2	80	.09	.053	5	20	.39	47	.14	3	1.84	.01	.04	1	1
27903	4	41	17	250	.8	9	5	261	1.22	9	5	ND	1	45	6.5	2	2	76	.60	.111	16	14	.27	133	.02	4	2.21	.02	.05	1	4
27904	1	5	34	55	.1	6	2	109	.96	2	5	ND	1	19	.2	2	2	21	.14	.037	7	12	.18	53	.07	4	1.20	.01	.04	1	1
27905	1	17	33	165	.3	15	8	479	2.70	9	5	ND	1	36	.3	2	2	51	.35	.042	8	21	.68	137	.10	2	2.25	.02	.07	1	2
27906	1	19	39	195	.3	15	9	685	2.93	13	5	ND	1	48	.4	2	2	52	.66	.062	7	21	.67	192	.08	2	2.50	.02	.08	1	2
27907	1	16	26	118	.6	14	11	912	2.93	6	5	ND	1	52	.6	2	2	54	.68	.093	12	20	.58	223	.06	3	2.63	.03	.07	1	3
27908	2	27	23	136	1.1	13	11	1597	4.36	6	5	ND	1	38	.4	2	2	80	.37	.162	9	21	.59	128	.02	2	3.36	.01	.06	1	1
27909	1	22	21	137	1.4	10	9	1895	2.21	2	6	ND	1	71	1.2	2	2	39	.82	.140	21	18	.41	176	.02	3	2.48	.01	.06	1	2
27910	1	14	28	126	.2	11	7	559	2.56	6	5	ND	1	36	.2	2	2	48	.41	.062	10	20	.58	113	.11	2	1.71	.02	.07	1	2
27911	1	10	25	93	.1	9	6	307	1.89	3	5	ND	1	40	.2	2	2	37	.36	.058	8	19	.48	111	.09	3	1.71	.03	.04	1	2
27912	1	10	21	97	.3	10	5	244	2.07	6	5	ND	1	32	.2	2	2	41	.27	.043	6	19	.49	80	.09	4	1.54	.02	.04	1	2
27913	1	16	28	229	.6	13	8	845	2.63	3	5	ND	1	46	1.4	2	2	47	.45	.122	8	22	.59	203	.04	2	2.42	.02	.06	1	5
27914	1	18	23	170	1.0	19	8	345	2.48	5	5	ND	1	52	.4	4	2	42	.33	.060	7	23	.69	147	.07	3	2.84	.01	.07	1	1
27915	1	19	28	122	1.2	19	8	261	2.00	4	5	ND	1	53	.4	2	2	53	.43	.089	12	29	.62	159	.07	3	2.94	.02	.10	1	2
27916	1	10	22	46	.3	6	4	185	2.93	5	5	ND	1	11	.2	2	3	61	.09	.053	7	18	.29	39	.12	2	1.77	.01	.04	2	1
27917	1	14	26	109	.1	12	9	306	2.56	8	5	ND	1	50	.2	2	2	57	.37	.061	8	24	.57	101	.13	4	2.15	.05	.06	1	5
27918	1	9	28	95	1.1	11	6	259	1.93	3	5	ND	1	46	.2	2	2	38	.39	.047	6	18	.49	83	.08	3	2.03	.02	.06	1	3
27919	1	10	31	141	1.0	16	7	336	1.91	4	5	ND	1	42	.4	2	2	35	.36	.057	7	23	.52	118	.06	3	2.32	.02	.07	1	3
27920	1	9	39	136	1.3	13	6	283	2.08	7	5	ND	1	26	.2	2	2	37	.22	.043	8	19	.51	119	.10	2	2.24	.01	.06	1	4
STANDARD C/AU-S	18	59	41	131	6.8	71	32	1044	3.95	37	15	6	38	53	18.3	15	19	56	.51	.090	37	56	.89	181	.09	36	1.88	.06	.14	14	46

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
27921	1	10	29	90	1.0	9	5	330	1.96	3	5	ND	2	26	.2	2	2	41	.25	.041	8	16	.59	62	.10	4	1.72	.02	.06	1	3
27922	1	10	29	83	1.0	10	6	357	2.00	3	5	ND	1	36	.2	2	2	40	.33	.049	9	19	.44	83	.11	3	1.63	.02	.06	1	9
27923	3	16	42	142	2.4	12	11	3082	3.12	10	5	ND	1	62	1.6	2	2	64	.99	.126	7	19	.59	121	.07	2	2.18	.04	.10	1	6
27924	2	19	33	119	3.4	14	11	4649	3.01	8	15	ND	2	46	1.9	2	2	60	.85	.158	17	25	.55	181	.06	3	2.79	.04	.07	1	2
27925	1	13	32	99	2.2	10	6	556	2.57	10	5	ND	1	30	.3	2	2	48	.46	.063	10	16	.53	70	.11	4	1.67	.03	.06	1	9
27926	2	18	39	152	2.4	12	9	2413	3.15	10	5	ND	1	53	.9	4	2	60	1.12	.115	14	21	.56	189	.07	3	2.44	.04	.09	1	36
27927	1	10	31	126	2.0	11	6	742	2.46	7	5	ND	1	35	.2	2	2	45	.57	.067	8	17	.58	131	.10	3	1.71	.03	.07	1	9
27928	1	5	20	45	.5	3	2	234	1.20	4	5	ND	1	14	.2	2	2	35	.15	.021	8	10	.30	46	.13	3	1.04	.01	.03	2	2
27929	1	21	42	114	.7	6	5	407	3.57	21	5	ND	1	10	.2	2	2	48	.10	.055	9	13	.41	44	.08	2	2.03	.01	.06	1	13
27930	1	17	62	204	1.9	13	7	378	3.27	30	5	ND	1	18	.2	2	2	47	.17	.078	11	20	.44	47	.11	2	2.71	.01	.05	1	11
27931	1	12	55	111	.9	7	5	409	4.15	23	5	ND	3	13	.2	2	2	64	.13	.072	9	18	.40	41	.13	2	1.99	.01	.05	1	12
27932	1	22	74	147	1.4	12	10	543	3.76	41	5	ND	4	12	.2	2	2	58	.15	.061	9	20	.57	53	.11	2	1.85	.01	.06	1	26
27933	1	17	36	102	1.0	10	6	394	3.51	25	5	ND	1	15	.2	2	2	63	.15	.043	8	20	.57	52	.12	2	2.10	.01	.05	1	29
27934	1	14	47	110	2.7	7	5	310	2.36	16	5	ND	1	12	.2	2	2	37	.11	.060	10	15	.51	61	.05	3	2.48	.01	.04	1	7
27935	1	13	48	89	1.3	6	4	323	2.50	14	5	ND	1	15	.2	2	2	39	.14	.054	10	11	.42	50	.05	2	1.55	.01	.04	1	16
27936	1	28	40	131	2.7	9	9	438	3.35	17	5	ND	1	22	.2	2	2	53	.35	.082	10	13	.61	135	.02	2	2.68	.01	.05	1	9
27937	1	14	32	159	.9	6	5	534	3.66	14	5	ND	1	11	.2	2	2	71	.15	.054	7	16	.85	70	.05	2	2.52	.01	.08	1	5
27938	1	13	25	83	.5	5	6	335	3.33	16	5	ND	1	13	.2	2	2	59	.16	.055	8	12	.44	56	.03	2	1.57	.01	.05	1	2
27939	2	26	14	77	.3	5	6	510	3.23	6	5	ND	1	62	.2	2	2	45	.67	.074	5	13	.68	77	.10	4	1.32	.02	.09	1	3
27940	1	23	15	87	.4	11	12	527	3.73	6	5	ND	1	36	.2	2	2	54	.62	.075	9	20	.56	75	.12	2	1.94	.01	.07	1	2
27941	2	31	20	101	.3	8	6	540	4.50	4	5	ND	1	50	.2	2	4	62	.21	.087	11	14	.83	113	.13	2	2.05	.02	.08	1	2
27942	4	48	59	180	.2	10	11	1080	6.83	11	5	ND	1	59	.2	4	2	86	.36	.122	9	15	1.22	137	.10	2	3.01	.03	.11	1	6
27943	4	56	59	166	1.0	10	13	1906	6.39	12	5	ND	1	87	.8	5	2	64	.85	.175	9	10	1.06	163	.04	2	2.96	.03	.14	1	7
27944	4	36	61	106	1.2	6	6	1011	6.51	13	5	ND	2	73	.2	2	3	64	.07	.137	13	10	.79	165	.07	2	2.27	.03	.14	1	2
27945	6	72	68	125	.8	8	6	939	8.77	18	5	ND	4	123	.5	3	2	88	.11	.151	12	9	1.32	195	.13	2	3.45	.04	.34	1	9
27946	6	40	74	89	1.4	6	5	737	6.95	14	5	ND	1	73	.2	2	2	118	.14	.159	11	6	1.03	136	.06	2	2.44	.03	.15	1	8
27947	7	74	88	133	.7	7	7	1153	9.24	22	5	ND	4	150	.4	5	2	93	.19	.177	16	8	1.41	192	.15	2	3.39	.07	.59	1	11
27948	7	38	81	72	1.6	4	3	486	6.52	17	5	ND	2	103	.2	2	2	61	.07	.205	14	6	.55	157	.05	2	1.91	.04	.21	1	1
27949	6	44	87	104	1.7	3	3	623	7.76	16	5	ND	2	98	.2	5	2	50	.11	.197	13	4	.75	110	.08	2	2.87	.03	.21	1	11
27950	7	42	94	106	1.3	5	4	618	8.72	10	5	ND	2	82	.5	3	2	79	.09	.153	8	8	.80	137	.07	2	2.61	.05	.15	1	6
27961	1	10	36	57	.7	6	4	206	2.35	6	5	ND	1	17	.2	2	2	39	.14	.062	12	14	.36	70	.07	2	2.18	.01	.03	1	1
27962	1	23	50	164	.5	12	7	656	3.04	8	5	ND	1	26	.2	2	2	54	.38	.067	16	20	.55	140	.08	3	2.42	.01	.06	1	1
27963	1	11	25	111	.4	9	6	383	2.53	4	5	ND	1	17	.2	2	2	47	.19	.034	9	17	.52	60	.12	4	1.54	.01	.04	1	1
27964	1	20	29	400	.5	12	7	444	3.05	9	5	ND	1	25	.5	2	2	57	.37	.044	11	22	.56	103	.14	3	2.03	.01	.06	1	2
27965	1	13	21	101	.7	10	6	318	4.19	6	5	ND	1	24	.2	2	2	62	.26	.108	7	21	.36	61	.11	5	1.78	.01	.04	1	1
27966	1	12	15	113	.5	14	7	320	4.25	9	5	ND	1	14	.2	2	2	73	.16	.106	8	28	.50	43	.17	5	2.65	.01	.03	1	1
STANDARD C/AU-S	18	58	39	131	6.9	70	32	1044	3.95	36	16	8	37	53	18.3	15	18	55	.51	.089	37	56	.91	181	.09	36	1.88	.06	.14	12	52

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
27967	2	7	19	66	.1	8	6	222	3.00	9	5	ND	1	13	.5	2	7	47	.11	.076	7	17	.30	48	.11	2	2.27	.01	.03	3	7
27968	1	15	19	83	.2	7	6	317	3.16	7	5	ND	1	15	.4	2	2	45	.14	.088	7	18	.35	43	.10	2	2.49	.01	.03	1	2
27969	1	11	57	151	.1	5	6	528	2.74	6	5	ND	1	20	.3	2	3	37	.16	.079	12	14	.37	112	.05	2	2.06	.01	.04	1	3
27970	1	9	23	92	.2	7	7	375	3.38	9	5	ND	2	16	.5	3	3	53	.17	.083	8	22	.38	47	.12	2	2.24	.01	.04	1	5
27971	2	15	40	106	.3	8	7	465	3.67	6	5	ND	1	11	.4	2	3	65	.12	.080	8	24	.25	42	.09	3	1.95	.01	.03	1	1
27972	1	13	10	79	.1	13	9	367	4.50	14	5	ND	1	17	.2	2	2	83	.24	.070	7	31	.36	69	.13	3	1.48	.01	.04	1	2
27973	2	7	25	93	.1	7	7	693	4.24	4	5	ND	1	20	.2	2	2	59	.20	.107	8	16	.38	52	.14	5	1.96	.01	.05	1	1
27974	1	10	12	76	.1	13	7	265	3.34	8	5	ND	2	16	.2	2	4	62	.15	.067	7	25	.31	55	.15	2	1.87	.01	.03	1	3
27975	1	10	14	47	.2	8	6	210	2.94	5	5	ND	1	13	.6	2	2	62	.13	.048	9	27	.21	38	.15	2	1.47	.01	.03	1	3
27976	1	5	11	36	.1	8	5	182	2.80	4	5	ND	1	12	.2	2	5	59	.12	.046	7	26	.21	34	.14	4	1.52	.01	.03	1	2
27977	1	8	19	55	.2	9	6	204	3.88	6	5	ND	1	19	.2	2	2	68	.15	.072	7	27	.27	52	.12	4	2.25	.01	.03	1	1
27978	1	8	15	71	.2	9	7	214	4.17	10	5	ND	1	17	.2	2	3	69	.15	.128	7	26	.29	55	.11	2	2.21	.01	.04	1	10
27979	1	8	15	78	.1	12	6	230	3.00	9	5	ND	1	12	.4	2	3	55	.12	.046	9	22	.32	47	.14	2	2.10	.01	.05	1	3
27980	1	7	24	62	.2	9	6	234	2.21	3	5	ND	1	16	.2	2	2	46	.14	.040	8	16	.33	49	.13	3	1.62	.01	.05	1	2
27981	1	7	17	65	.4	9	5	233	2.02	5	5	ND	1	30	.4	2	2	41	.28	.034	9	15	.36	68	.10	4	1.60	.01	.05	1	3
27982	1	22	14	111	.7	17	10	613	3.35	14	5	ND	1	65	.7	2	2	64	1.06	.085	11	28	.65	109	.09	5	2.26	.05	.13	1	1
27983	1	11	17	76	.2	13	7	264	2.14	5	5	ND	1	31	.5	2	3	50	.43	.032	9	19	.47	67	.12	5	1.58	.02	.06	1	2
27984	1	14	19	82	.3	14	9	303	2.78	7	5	ND	1	21	.2	2	2	57	.18	.039	9	24	.54	69	.13	2	2.12	.01	.07	1	2
27985	1	6	31	72	.2	9	5	223	1.88	4	5	ND	1	13	.2	2	2	42	.13	.025	9	18	.33	43	.12	2	1.52	.01	.05	1	1
27986	1	10	19	76	.2	13	8	265	3.11	10	5	ND	1	13	.2	2	6	61	.12	.044	8	24	.36	59	.12	2	2.25	.01	.06	1	1
27987	2	12	23	84	.2	11	9	306	6.00	22	5	ND	5	10	.5	2	4	90	.10	.117	6	32	.44	47	.15	3	5.75	.02	.05	1	2
27988	1	9	20	69	.2	9	6	242	3.16	10	5	ND	1	10	.2	2	4	56	.10	.062	7	22	.27	47	.11	2	2.24	.01	.04	1	1
27989	1	12	23	57	.2	10	5	218	2.67	10	5	ND	1	11	.3	2	2	47	.11	.054	7	21	.26	40	.10	2	2.20	.01	.04	1	1
27990	1	8	17	95	.1	11	8	379	3.92	11	5	ND	1	13	.6	2	2	69	.13	.072	7	27	.41	49	.12	4	2.47	.01	.05	1	1
27991	1	10	11	60	.1	8	6	296	2.91	7	5	ND	1	14	.2	2	2	52	.14	.064	8	20	.27	42	.11	2	2.02	.01	.03	1	1
27992	2	11	28	99	.1	8	8	375	4.61	10	5	ND	1	12	.5	2	5	85	.12	.039	7	26	.33	41	.11	2	1.71	.01	.03	1	2
27993	1	12	33	156	.2	12	8	314	3.99	24	5	ND	1	12	.2	2	2	69	.12	.067	8	27	.40	83	.10	2	2.68	.01	.04	1	2
27994	1	11	25	109	.3	13	10	338	5.08	15	5	ND	1	14	.2	2	2	94	.15	.108	8	39	.38	46	.12	2	3.30	.01	.05	1	2
27995	1	13	23	58	.1	14	9	271	3.52	9	5	ND	2	15	.2	2	3	72	.15	.040	8	30	.33	47	.15	4	1.72	.01	.04	1	7
27996	1	19	22	76	.1	21	14	395	4.60	17	5	ND	2	23	.5	2	2	93	.20	.097	7	36	.64	80	.15	5	3.06	.02	.07	1	3
27997	1	10	14	59	.2	12	6	200	2.95	9	5	ND	1	15	.4	2	2	56	.12	.045	8	25	.24	53	.12	2	1.83	.01	.03	1	3
27998	2	14	22	114	.1	9	7	937	2.50	8	5	ND	1	36	.7	2	2	49	.41	.041	15	23	.28	91	.09	2	1.62	.01	.04	1	1
27999	1	10	13	95	.2	14	9	327	4.46	10	5	ND	1	14	.5	2	2	82	.13	.128	7	32	.40	48	.13	2	2.56	.01	.05	1	2
28000	2	11	22	62	.2	12	9	271	4.73	7	5	ND	1	19	.8	2	2	92	.13	.065	7	33	.31	61	.10	2	2.14	.01	.05	1	1
29385	1	9	19	59	.4	12	8	350	4.87	10	5	ND	1	9	.2	2	2	113	.09	.056	7	32	.46	36	.18	2	1.83	.01	.06	1	2
29386	2	16	25	88	.1	15	11	374	6.12	8	5	ND	1	14	.5	2	2	117	.15	.056	8	45	.55	54	.12	2	2.33	.01	.06	1	4
STANDARD C/AU-S	18	58	41	131	7.0	72	31	1051	3.94	43	20	7	38	53	18.4	15	21	55	.51	.095	37	56	.89	181	.07	34	1.88	.06	.13	13	47

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	M ppm	Au* ppb
29387	1	14	23	80	.2	13	7	358	2.96	7	5	ND	1	17	.2	2	2	60	.21	.058	8	25	.55	68	.11	4	2.37	.01	.07	1	2
29388	1	17	24	68	2.2	9	5	188	1.38	3	5	ND	1	45	.9	2	2	27	.39	.166	7	14	.26	90	.01	3	1.76	.03	.06	1	2
29389	1	12	22	92	.6	13	7	310	2.42	4	5	ND	1	23	.2	2	2	52	.25	.055	9	24	.56	86	.11	2	2.04	.01	.07	1	1
29390	1	15	20	255	.8	13	8	640	2.85	2	5	ND	1	45	1.0	2	2	52	.61	.140	11	22	.55	277	.04	3	2.72	.02	.08	2	1
29391	1	21	17	177	.7	12	7	270	2.43	2	5	ND	1	43	.4	2	2	47	.31	.121	15	25	.46	208	.05	2	2.80	.02	.05	1	5
29392	1	27	3	185	.4	10	7	408	2.89	2	5	ND	1	29	.2	2	2	55	.40	.078	10	18	.50	134	.07	2	2.06	.01	.06	1	3
29393	1	17	13	82	.2	9	8	483	2.90	4	5	ND	1	32	.2	2	6	55	.36	.063	12	20	.52	126	.10	2	1.90	.02	.07	1	2
29394	1	13	12	52	.1	7	5	220	2.00	2	5	ND	1	14	.2	2	2	41	.14	.049	8	13	.31	61	.05	4	1.60	.01	.05	1	1
29395	1	11	16	39	.1	5	3	127	1.46	2	5	ND	1	16	.2	2	2	30	.12	.054	8	11	.11	53	.03	3	1.04	.01	.05	1	1
29396	1	12	12	69	.2	8	7	429	2.34	2	5	ND	1	15	.2	2	2	46	.19	.054	8	17	.35	48	.07	3	1.23	.01	.06	1	1
29397	1	12	21	84	.1	12	6	317	2.20	2	5	ND	1	19	.2	2	2	48	.24	.044	8	22	.43	80	.08	2	1.99	.01	.08	1	2
29398	1	14	20	364	.1	10	6	377	2.12	2	5	ND	1	21	1.4	2	6	50	.32	.044	9	17	.45	97	.07	2	1.79	.01	.06	1	1
29399	1	3	35	59	.1	4	2	151	1.20	2	5	ND	1	12	.2	2	2	36	.16	.021	9	11	.07	27	.12	2	.57	.01	.03	1	1
29400	1	12	29	202	.2	10	6	326	2.46	2	5	ND	1	14	.2	2	2	58	.16	.027	8	20	.48	80	.09	3	1.59	.01	.06	1	1
29401	1	13	25	83	.2	6	6	336	3.03	6	5	ND	1	12	.2	2	2	54	.14	.052	9	18	.31	33	.09	5	1.28	.01	.04	1	2
29402	1	11	34	86	1.1	7	4	299	1.79	3	5	ND	1	10	.2	2	4	34	.12	.043	8	15	.34	39	.06	3	1.77	.01	.04	1	1
29403	1	12	97	89	.4	6	4	311	1.82	2	5	ND	1	18	.2	5	3	42	.21	.043	7	12	.25	58	.05	4	1.34	.01	.03	1	3
29404	1	23	50	80	.8	5	4	267	1.81	2	5	ND	1	14	.2	2	2	34	.14	.052	8	13	.25	52	.03	2	1.33	.01	.04	1	2
29405	1	10	32	57	.6	7	3	219	1.50	2	5	ND	1	20	.2	2	3	34	.20	.041	8	13	.18	59	.05	3	.93	.01	.04	1	2
29406	1	15	24	81	.4	8	6	474	2.43	4	6	ND	1	13	.2	2	2	46	.14	.090	8	20	.34	40	.07	3	1.89	.01	.05	1	7
29407	1	21	21	73	.8	14	9	319	2.65	5	5	ND	1	23	.2	2	2	62	.19	.060	8	22	.77	77	.06	2	1.92	.02	.09	1	1
29408	1	13	39	65	.7	6	4	233	2.12	4	5	ND	1	18	.2	2	3	39	.18	.059	8	15	.20	52	.04	2	1.30	.01	.05	1	1
29409	1	60	30	148	.6	6	3	326	1.70	2	5	ND	1	17	.4	2	3	33	.15	.060	9	14	.21	101	.02	3	1.47	.01	.04	1	1
29410	1	6	25	48	.6	5	3	175	1.62	2	5	ND	1	13	.2	2	2	33	.12	.052	7	16	.16	42	.06	3	1.44	.01	.04	1	1
29411	1	12	37	104	.2	8	5	313	2.69	3	5	ND	1	11	.2	2	6	43	.12	.057	7	19	.34	50	.08	3	2.35	.01	.04	1	2
29412	1	9	35	140	.4	5	4	217	1.76	2	5	ND	1	9	.2	2	2	36	.10	.038	8	14	.24	35	.05	2	1.45	.01	.03	1	5
29413	2	192	27	5196	.2	12	7	1174	2.53	6	5	ND	1	71	53.8	2	2	43	1.92	.182	21	19	.50	596	.03	4	2.64	.03	.10	2	2
29414	1	72	9	1362	.9	8	6	810	1.42	3	5	ND	1	106	18.7	2	2	25	2.88	.146	7	9	.30	464	.02	4	1.38	.02	.05	1	2
29415	1	140	19	786	.9	10	6	539	1.89	2	5	ND	1	44	7.0	2	2	39	.91	.129	10	16	.46	428	.03	2	1.96	.01	.06	2	2
29416	1	76	14	561	1.2	9	8	614	1.94	3	5	ND	1	74	4.6	2	2	38	1.44	.194	9	14	.40	382	.01	4	2.15	.02	.07	1	1
29417	1	47	10	193	1.0	7	4	289	.96	7	5	ND	1	31	2.1	6	2	19	.52	.110	7	10	.15	167	.01	4	1.11	.01	.03	1	5
29418	1	45	16	225	2.3	16	8	575	2.95	3	5	ND	1	61	.8	2	3	55	.77	.244	14	21	.58	228	.02	2	3.25	.01	.08	1	4
29419	1	15	7	210	.6	8	6	265	2.41	4	5	ND	1	29	.8	2	2	47	.44	.063	9	16	.39	125	.07	4	1.84	.01	.04	1	1
29420	1	21	14	409	1.1	9	7	445	2.09	2	5	ND	1	37	3.2	2	2	40	.66	.148	11	17	.47	154	.03	4	2.09	.02	.08	1	2
29421	1	10	26	65	3.8	7	3	257	1.20	2	7	ND	1	28	.3	2	3	25	.24	.268	8	13	.18	118	.01	6	1.48	.01	.06	1	4
29422	1	11	22	217	2.6	9	8	503	5.21	5	5	ND	1	12	.2	2	8	93	.20	.148	7	35	1.24	56	.06	5	5.10	.01	.04	1	3
STANDARD C/AU-S	18	58	36	131	6.7	73	31	1053	3.97	41	21	6	38	53	18.6	14	20	56	.52	.095	37	55	.90	181	.07	37	1.89	.06	.13	12	46

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
29423	1	13	26	70	.9	11	6	308	2.15	11	5	ND	1	18	.2	2	2	48	.18	.051	8	24	.51	64	.10	2	1.80	.01	.07	1	3
29424	1	10	32	29	.4	8	3	150	1.11	3	5	ND	1	21	.6	2	2	27	.13	.047	9	16	.17	57	.07	4	1.20	.01	.05	1	1
29425	1	13	19	82	.6	16	9	383	3.42	5	5	ND	1	14	.4	2	4	83	.15	.060	6	31	.73	56	.13	4	1.82	.01	.09	1	2
29426	1	12	22	50	.7	9	6	263	3.31	13	5	ND	1	10	.2	2	2	58	.10	.077	8	24	.38	47	.11	2	2.95	.01	.05	1	1
29427	1	13	30	89	.6	16	10	368	3.70	7	5	ND	1	14	.6	2	4	84	.17	.069	7	39	.75	55	.15	2	2.90	.02	.06	1	2
29428	1	12	25	61	1.0	9	5	212	2.17	7	5	ND	1	15	.6	2	2	47	.10	.068	8	24	.34	70	.08	2	3.18	.01	.04	1	2
29429	1	15	9	47	5.4	9	4	265	.98	2	5	ND	1	29	.2	2	2	19	.22	.304	10	14	.19	118	.01	4	2.67	.02	.05	1	2
29430	1	20	9	40	3.6	7	5	816	1.12	2	5	ND	1	30	1.2	2	2	24	.32	.264	8	9	.18	75	.01	2	1.81	.02	.06	1	2
29431	1	20	6	64	2.8	8	4	396	1.11	2	5	ND	1	46	1.9	2	2	20	.49	.298	9	14	.15	121	.01	3	1.73	.02	.08	1	2
29432	1	19	12	132	.9	8	6	560	2.07	2	5	ND	1	45	1.4	2	2	41	.75	.135	10	16	.51	293	.03	4	1.98	.02	.08	1	2
29433	1	19	14	48	2.0	8	5	192	1.44	3	5	ND	1	52	.8	2	2	28	.45	.159	11	17	.31	111	.01	2	1.89	.02	.07	1	1
29434	1	42	8	798	1.6	16	9	1061	3.32	2	5	ND	1	85	19.1	2	2	49	1.70	.266	13	20	.52	363	.03	3	3.47	.02	.13	1	1
29435	1	42	14	939	.4	11	7	565	2.67	6	5	ND	1	44	7.3	2	2	47	.88	.107	14	19	.55	173	.07	2	2.01	.02	.08	1	2
29436	1	52	14	477	2.9	12	7	358	2.25	2	5	ND	1	54	3.6	2	2	41	.96	.206	11	18	.57	247	.03	3	2.63	.01	.08	1	2
29437	1	78	24	360	3.9	8	6	1143	1.68	2	5	ND	1	80	6.7	2	2	31	1.76	.323	18	11	.33	520	.01	3	2.03	.01	.07	1	1
29438	1	107	65	356	1.9	6	4	501	1.55	2	5	ND	1	63	3.6	2	2	27	1.51	.289	23	14	.29	547	.01	2	2.12	.01	.05	1	1
29439	1	23	67	91	.3	5	2	178	1.21	3	5	ND	1	16	.3	2	2	27	.21	.051	9	13	.16	93	.04	2	1.16	.01	.04	1	1
29440	1	54	17	115	.6	7	5	248	1.78	2	5	ND	1	15	.5	2	2	35	.21	.074	9	16	.33	115	.05	2	1.49	.01	.04	1	1
29441	1	23	17	73	.6	9	5	311	2.60	6	5	ND	1	11	.3	3	2	47	.13	.078	8	22	.34	43	.07	4	1.84	.01	.04	1	3
29442	1	11	21	33	.2	5	3	220	1.43	2	5	ND	1	14	.2	2	2	30	.13	.046	8	13	.24	52	.04	2	1.24	.01	.04	1	1
29443	1	13	30	66	.8	7	5	284	2.36	2	5	ND	1	12	.2	2	2	42	.14	.085	8	20	.35	46	.06	2	2.46	.01	.04	1	1
29444	1	13	21	46	.3	9	4	242	2.14	4	5	ND	1	14	.2	2	3	40	.13	.070	8	17	.29	47	.07	4	1.70	.01	.05	1	1
29445	1	10	25	52	.4	8	5	284	2.04	4	5	ND	1	12	.2	3	2	43	.12	.034	9	15	.37	50	.09	2	1.32	.01	.05	1	1
29446	1	5	13	1	.1	3	2	96	.87	5	5	ND	1	8	.2	6	2	20	.09	.025	5	8	.09	26	.04	3	.55	.01	.02	1	2
29447	2	7	35	45	.6	4	4	239	2.87	2	5	ND	1	15	.2	2	3	43	.13	.046	5	13	.22	36	.06	2	1.28	.01	.03	5	1
29448	1	8	31	39	.4	8	6	280	2.75	5	5	ND	1	17	.2	4	2	61	.14	.046	8	18	.30	49	.10	3	1.31	.01	.04	1	2
29449	1	6	24	10	.4	4	2	130	1.44	2	5	ND	1	13	.2	2	2	33	.11	.043	8	12	.14	33	.05	3	1.05	.01	.03	1	1
29450	1	10	26	37	.7	8	4	218	1.69	6	5	ND	1	11	.2	2	2	34	.10	.060	8	15	.26	40	.05	2	1.45	.01	.04	1	1
30006	1	13	24	33	.2	7	4	217	2.50	4	5	ND	1	12	.2	2	2	43	.11	.061	7	17	.27	46	.06	2	1.87	.01	.03	1	1
30007	1	17	27	61	.8	12	8	335	2.71	2	5	ND	1	14	.2	2	2	58	.16	.073	9	26	.67	78	.07	2	2.77	.01	.05	1	1
30008	1	6	21	36	.1	5	3	143	1.58	2	5	ND	1	12	.2	2	3	31	.10	.060	7	12	.15	40	.04	2	1.11	.01	.04	1	1
30009	1	9	32	90	.1	8	4	307	1.66	2	5	ND	1	11	.2	2	4	36	.11	.027	8	15	.32	88	.07	2	1.54	.01	.04	1	1
30010	1	9	22	67	.3	8	5	236	2.19	2	5	ND	1	10	.2	2	2	43	.11	.056	8	18	.27	30	.07	2	1.42	.01	.04	1	1
30011	1	9	15	48	.1	5	4	157	1.41	3	5	ND	1	11	.2	2	3	30	.12	.038	7	14	.16	35	.07	2	.85	.01	.03	1	1
30012	1	8	42	48	.1	5	2	128	.94	2	5	ND	1	11	.3	2	4	21	.14	.037	9	9	.09	52	.03	2	.93	.01	.04	1	1
30013	1	83	16	242	2.6	8	3	1074	.94	2	5	ND	1	68	15.2	2	2	12	2.07	.320	47	9	.10	361	.01	4	1.59	.01	.06	1	3
STANDARD C/AU-S	18	59	36	131	6.6	71	31	1051	3.95	42	18	7	37	52	18.8	15	21	55	.51	.094	37	56	.89	181	.07	35	1.89	.06	.13	13	50


SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
30014	1	22	16	518	.8	9	6	668	1.83	2	5	ND	1	49	11.7	2	2	38	.76	.176	12	16	.46	505	.03	3	1.92	.01	.07	1	1
30015	1	31	44	300	1.7	12	4	202	2.17	7	5	ND	2	22	2.4	2	2	42	.20	.141	9	24	.33	262	.03	4	3.71	.01	.07	1	2
30016	1	14	18	123	.7	11	6	340	2.29	2	5	ND	1	25	.3	2	2	48	.23	.077	10	20	.50	180	.06	2	2.15	.01	.06	1	2
30017	1	11	13	70	.3	8	5	287	1.82	2	5	ND	2	16	.2	2	2	42	.16	.027	7	17	.50	59	.10	4	1.43	.01	.05	1	1
30018	3	103	27	214	6.8	12	8	3684	2.63	14	5	ND	1	71	5.1	2	2	46	1.38	.437	40	21	.37	397	.04	4	3.13	.01	.05	1	3
30019	2	19	18	164	.5	10	6	2800	2.46	6	5	ND	1	39	3.5	2	2	42	.75	.398	56	21	.31	824	.03	3	3.32	.02	.05	1	3
30020	1	6	16	48	.4	6	4	218	2.39	7	5	ND	1	11	.2	2	2	51	.11	.066	8	21	.27	53	.10	3	1.96	.01	.03	1	1
30021	1	13	17	63	1.7	8	5	225	3.17	8	5	ND	1	15	.2	3	2	59	.13	.093	8	27	.33	53	.09	2	2.70	.01	.04	1	20
30022	1	10	24	46	.4	5	3	239	2.01	2	5	ND	1	27	.2	2	2	46	.30	.055	7	18	.11	54	.06	2	.80	.01	.03	1	2
30023	1	8	28	75	.1	7	4	372	2.73	8	5	ND	1	15	.2	2	2	49	.14	.085	7	20	.26	38	.07	3	1.38	.01	.02	1	2
30024	1	7	20	39	.1	4	2	139	1.33	4	5	ND	1	11	.2	2	3	30	.11	.045	8	11	.12	49	.04	2	.85	.01	.02	1	4
30025	1	7	23	70	.4	8	4	275	2.51	10	5	ND	1	17	.2	2	2	51	.15	.069	8	18	.33	37	.09	2	1.54	.01	.04	1	4
30026	1	10	30	42	.2	5	4	257	1.97	2	5	ND	1	17	.2	2	2	45	.15	.053	8	13	.25	37	.06	3	1.10	.01	.04	1	2
30027	1	12	32	97	.1	12	6	321	3.24	17	5	ND	1	12	.2	2	2	59	.11	.071	9	24	.38	49	.10	2	2.79	.01	.03	1	4
30028	1	11	37	59	.1	6	3	224	2.08	5	5	ND	1	14	.2	3	3	52	.12	.045	8	17	.22	32	.10	4	1.21	.01	.04	1	1
30029	1	43	24	46	1.5	14	5	137	1.67	2	5	ND	1	15	.9	3	2	31	.09	.191	9	22	.42	61	.01	3	2.27	.01	.03	1	1
30030	1	11	29	59	.2	7	3	203	2.58	7	5	ND	2	10	.2	2	2	52	.09	.052	8	20	.24	35	.09	2	1.91	.01	.04	1	3
30031	1	13	33	99	.1	9	5	327	2.87	8	5	ND	1	12	.2	2	2	56	.11	.055	8	23	.36	39	.11	2	1.89	.01	.04	1	3
30032	1	6	28	103	.8	4	2	126	1.29	2	5	ND	1	13	.6	2	2	28	.15	.057	8	13	.16	49	.04	3	1.49	.01	.02	1	1
30033	1	7	17	69	.4	8	4	225	2.02	6	5	ND	2	12	.2	2	3	40	.13	.059	7	20	.27	42	.09	2	1.20	.01	.04	1	1
30034	1	6	26	26	.5	3	1	85	.80	2	5	ND	1	11	.2	2	2	21	.09	.045	8	11	.07	34	.04	2	.78	.01	.02	1	3
30035	1	10	19	32	.4	3	1	101	.82	2	5	ND	1	15	.2	2	3	23	.13	.049	9	11	.08	65	.05	3	.77	.01	.02	1	2
30036	1	8	18	29	.5	4	2	110	1.24	5	5	ND	1	11	.2	2	2	30	.09	.056	8	16	.11	30	.06	3	.94	.01	.03	2	2
30037	1	17	12	62	1.1	14	7	263	2.56	10	5	ND	1	27	.2	2	2	51	.28	.091	8	36	.72	68	.10	2	3.12	.06	.05	1	3
30038	1	10	18	27	.4	4	2	113	1.41	4	5	ND	1	15	.2	2	3	34	.13	.058	8	17	.14	31	.08	3	1.26	.01	.02	1	1
30039	1	12	18	47	.3	8	3	135	2.31	7	5	ND	1	13	.2	3	2	47	.10	.085	7	25	.23	41	.05	2	1.79	.01	.02	1	1
30040	1	7	17	63	.5	9	5	236	2.86	8	5	ND	3	11	.2	2	2	51	.10	.079	7	24	.33	51	.10	2	3.30	.01	.04	1	24
30041	1	10	20	29	.7	3	2	113	1.30	5	5	ND	2	9	.2	2	2	34	.07	.034	8	11	.11	37	.07	3	1.11	.01	.03	1	2
30042	1	6	18	36	.3	5	3	154	2.22	6	5	ND	2	10	.2	2	2	47	.08	.046	8	19	.18	38	.11	2	2.04	.01	.03	1	1
30043	1	18	14	84	1.2	11	6	374	1.64	4	5	ND	2	110	1.0	2	2	24	1.17	.135	14	14	.24	131	.02	4	1.66	.02	.10	1	4
30044	1	16	21	49	1.1	7	3	121	1.34	10	5	ND	1	20	.3	2	2	26	.14	.069	9	14	.17	44	.03	3	1.35	.01	.05	1	2
30045	1	15	21	72	.5	13	8	298	2.48	11	5	ND	2	14	.2	2	2	60	.11	.040	8	22	.71	49	.13	2	1.77	.01	.07	1	3
30046	1	2	20	30	.2	5	2	129	1.00	4	5	ND	2	12	.2	2	3	30	.09	.020	8	11	.17	27	.12	3	.78	.01	.04	2	3
30047	1	2	17	33	.1	6	3	127	1.22	7	5	ND	1	10	.2	2	2	33	.08	.025	8	12	.17	28	.11	3	.94	.01	.03	1	2
30048	1	50	118	1118	.1	11	7	1100	2.08	5	5	ND	1	37	8.1	2	2	43	.56	.127	11	20	.41	136	.04	3	1.54	.01	.04	1	2
30049	1	15	23	85	.2	6	2	188	1.69	10	5	ND	2	13	.5	2	2	37	.12	.068	7	14	.12	35	.07	2	.81	.01	.04	1	1
STANDARD C/AU-S	19	57	40	130	7.0	72	31	1046	3.95	39	25	7	40	52	18.6	15	22	60	.51	.094	40	61	.89	183	.09	33	1.89	.06	.13	14	48

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Tl %	B ppm	Al %	Na %	K %	Mn ppm	Au* ppb
30050	2	8	113	88	.4	5	3	404	2.12	6	5	ND	1	17	.2	2	2	40	.27	.077	8	14	.16	53	.07	2	1.08	.01	.05	1	14
30051	1	13	21	75	.5	13	10	916	3.94	8	5	ND	1	13	.2	2	3	63	.16	.106	10	26	.46	82	.14	3	3.06	.01	.06	2	1
30052	1	17	19	48	.8	6	5	326	3.00	4	5	ND	1	12	.2	2	2	59	.13	.094	8	21	.28	40	.11	3	1.59	.01	.04	1	6
30053	1	10	14	61	.6	10	7	301	3.02	4	5	ND	1	11	.2	2	2	52	.13	.082	7	25	.35	43	.13	2	2.70	.01	.04	2	4
30054	1	7	14	63	.4	7	6	821	2.96	2	5	ND	1	19	.2	3	4	50	.21	.099	7	18	.26	80	.07	2	1.33	.01	.04	1	3
30055	1	9	15	68	.4	8	6	631	3.84	5	5	ND	1	18	.2	2	3	67	.20	.088	7	22	.33	60	.11	2	1.74	.01	.04	1	2
30056	1	14	16	64	.5	7	6	332	3.93	2	5	ND	1	20	.2	2	2	62	.23	.121	7	21	.32	51	.10	2	2.01	.01	.04	1	3
30057	1	11	16	75	.5	6	6	415	3.91	5	5	ND	1	20	.2	3	3	70	.22	.081	7	22	.25	68	.10	3	1.35	.01	.04	2	1
30058	1	9	19	53	.1	5	5	228	3.29	7	5	ND	1	15	.2	2	2	59	.14	.056	6	21	.23	41	.11	2	1.29	.01	.02	1	1
30059	1	10	17	66	.2	12	8	249	3.26	6	5	ND	1	17	.8	2	2	65	.16	.052	10	33	.26	52	.17	3	1.72	.01	.03	1	1
30060	1	11	14	86	.1	14	7	412	3.55	4	5	ND	1	28	.4	2	2	72	.27	.068	10	34	.27	83	.17	4	1.76	.01	.03	1	1
30061	1	12	27	147	.1	11	8	352	3.50	14	5	ND	1	16	.2	2	2	59	.25	.095	7	25	.39	33	.09	3	1.97	.01	.03	2	2
30062	1	7	20	75	.1	7	6	332	3.23	6	5	ND	1	14	.2	2	2	63	.13	.085	8	21	.24	74	.11	3	1.50	.01	.03	1	1
30063	1	11	20	62	.1	7	5	362	2.97	5	5	ND	1	23	.2	2	6	64	.27	.061	10	22	.25	168	.12	2	1.40	.01	.04	1	1
30064	1	4	20	46	.1	3	4	185	2.43	3	5	ND	1	17	.2	2	2	53	.15	.036	8	15	.19	67	.11	3	1.11	.01	.03	1	1
30065	1	9	18	101	.1	7	7	354	3.68	9	5	ND	1	14	.2	2	2	63	.15	.069	8	23	.37	40	.10	2	1.96	.01	.03	2	1
30066	1	7	15	60	.1	5	4	215	2.42	4	5	ND	1	23	.4	2	2	49	.24	.053	8	17	.19	83	.12	2	1.03	.01	.03	1	6
30067	1	19	13	281	.1	5	5	616	1.71	3	5	ND	1	38	3.8	3	2	36	.67	.072	8	14	.20	182	.07	3	.94	.01	.04	1	1
30068	1	10	19	69	.3	7	6	249	3.18	5	5	ND	1	24	.5	2	2	60	.24	.065	7	21	.23	80	.08	2	1.32	.01	.04	2	2
30069	1	23	38	135	.1	11	10	793	4.25	8	5	ND	1	15	.2	2	2	66	.16	.098	9	21	.59	108	.08	4	2.51	.01	.05	2	1
30070	1	10	17	85	.1	9	7	951	2.54	5	5	ND	1	31	.7	3	3	52	.41	.044	9	19	.40	81	.10	4	1.47	.01	.04	1	1
30071	1	9	11	72	.2	7	7	975	2.53	4	5	ND	1	39	.5	3	2	50	.56	.082	8	19	.34	156	.05	2	1.22	.01	.05	1	1
30072	1	10	14	31	.3	3	2	193	1.51	2	5	ND	1	27	.2	3	5	36	.23	.043	9	12	.10	66	.07	2	.70	.01	.04	1	2
30073	1	10	10	66	.6	7	6	938	4.04	2	5	ND	1	18	.2	2	2	57	.18	.163	7	19	.26	79	.08	2	1.55	.01	.04	2	2
30074	1	8	24	58	.5	6	4	366	2.82	4	5	ND	1	13	.2	2	2	49	.11	.060	7	17	.22	47	.09	5	1.46	.01	.03	2	1
30075	1	5	36	68	.2	5	3	179	2.11	4	5	ND	1	10	.2	2	2	44	.09	.040	8	16	.16	34	.10	2	1.43	.01	.03	1	4
30076	1	8	20	53	.1	4	2	134	1.62	3	5	ND	1	11	.6	2	2	36	.09	.042	8	14	.12	47	.06	2	.94	.01	.03	1	1
30077	1	17	136	108	.1	6	3	195	1.74	3	5	ND	1	16	.9	2	2	39	.15	.041	9	14	.19	57	.07	2	1.04	.01	.05	1	2
30078	1	87	412	918	.7	11	7	459	2.53	6	5	ND	1	19	3.2	2	2	52	.24	.087	11	20	.51	96	.06	2	2.27	.01	.06	1	5
30079	1	10	25	98	.2	9	5	235	2.51	8	7	ND	1	12	.5	3	3	55	.14	.035	9	19	.40	59	.12	2	1.83	.01	.05	1	2
30080	1	6	20	30	.1	1	2	95	1.20	2	5	ND	1	11	.2	2	2	26	.08	.039	9	11	.08	29	.05	2	.90	.01	.03	1	1
30081	1	11	22	73	.3	10	4	222	1.80	2	5	ND	1	18	.3	2	2	39	.17	.040	9	16	.36	65	.08	2	1.60	.01	.05	1	1
30082	1	11	18	33	1.0	7	4	144	1.50	3	5	ND	1	17	.3	3	2	33	.14	.042	7	16	.21	49	.07	2	.99	.02	.04	2	3
30083	1	17	25	81	1.3	12	7	354	2.30	4	5	ND	1	49	.3	2	2	48	.63	.171	10	17	.44	97	.02	2	2.52	.02	.08	1	2
30084	1	22	20	110	1.9	11	6	516	2.32	3	5	ND	1	92	1.3	2	2	42	1.77	.179	15	18	.43	153	.04	2	2.59	.02	.08	2	2
30085	2	7	20	52	.1	10	5	169	2.98	6	5	ND	1	18	.2	2	3	72	.22	.070	6	27	.27	34	.11	2	1.51	.01	.04	1	1
STANDARD C/AU-S	18	58	41	131	6.7	68	31	1051	3.94	40	19	7	37	53	18.4	14	21	55	.51	.093	37	55	.89	181	.07	34	1.89	.06	.14	11	46








SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
30086	1	9	32	43	.3	4	3	139	1.14	2	5	ND	1	21	.6	2	2	33	.17	.047	8	14	.17	37	.11	2	1.27	.01	.04	2	1
30087	1	15	20	85	.6	13	9	295	2.52	2	5	ND	1	43	.6	2	2	61	.31	.073	8	24	.74	65	.10	3	2.07	.04	.06	1	3
30088	1	8	15	41	.2	4	4	131	2.64	4	5	ND	1	11	.2	2	2	70	.08	.041	7	20	.18	30	.13	2	1.25	.01	.03	1	1
30089	1	17	19	84	.6	11	9	342	4.88	9	5	ND	1	24	.2	2	3	111	.23	.079	6	32	.61	77	.12	2	2.18	.02	.07	1	1
30090	3	39	115	582	3.4	8	5	642	2.12	20	5	ND	1	33	2.6	2	2	39	.31	.084	15	16	.29	76	.06	2	2.13	.01	.06	1	46
30091	1	9	24	47	.1	6	5	187	2.80	2	5	ND	1	14	.2	2	2	64	.10	.044	8	25	.24	54	.13	2	1.42	.01	.04	1	2
30092	1	10	24	61	.2	8	5	201	3.08	4	5	ND	1	17	.2	2	2	76	.21	.066	7	23	.25	64	.12	2	1.32	.01	.05	1	1
30093	1	14	24	97	1.6	10	7	287	2.77	6	5	ND	1	40	.8	2	4	65	.40	.059	7	21	.54	56	.10	2	1.72	.02	.06	1	2
30094	2	30	29	273	3.0	14	8	841	2.65	5	5	ND	1	97	2.5	2	3	51	1.12	.248	12	19	.52	115	.02	2	2.98	.01	.10	1	3
30095	1	32	14	351	1.6	11	8	577	2.41	26	5	ND	1	75	2.1	2	3	52	1.71	.140	12	21	.56	92	.07	2	2.18	.05	.09	1	3
30096	1	15	8	116	.5	9	8	1001	2.15	4	5	ND	1	73	.6	2	2	43	2.10	.128	9	18	.44	102	.07	3	1.72	.03	.08	2	3
30097	1	25	22	116	1.7	13	10	1047	2.75	2	8	ND	1	65	1.6	2	3	53	1.11	.170	13	23	.47	138	.05	2	2.61	.02	.09	1	2
30098	1	16	7	80	2.9	8	3	1675	.67	2	5	ND	1	176	2.7	2	2	13	3.46	.172	12	7	.11	86	.01	7	1.12	.02	.06	2	1
30099	1	18	11	97	.6	16	11	392	3.28	2	5	ND	1	32	.5	2	2	74	.36	.067	9	26	.79	85	.13	2	2.73	.03	.07	1	1
30101	1	9	9	64	.2	7	5	188	2.91	2	5	ND	1	16	.2	2	5	62	.14	.034	7	22	.19	46	.11	2	1.11	.01	.04	1	2
30102	2	22	20	120	.5	14	7	238	3.51	8	5	ND	1	29	.4	2	2	65	.33	.054	7	26	.37	111	.12	2	1.99	.01	.04	1	1
30103	1	39	37	381	.2	11	8	485	3.01	9	5	ND	1	38	3.0	2	5	58	.53	.092	11	34	.35	177	.06	2	2.45	.01	.06	1	4
30104	1	26	32	129	.2	10	7	405	2.90	10	6	ND	1	31	.3	2	3	50	.40	.053	20	28	.37	89	.08	2	1.95	.02	.03	1	1
30105	2	10	18	82	.2	8	6	233	4.32	5	5	ND	1	18	.2	2	2	73	.17	.049	8	24	.25	66	.10	2	1.75	.01	.03	1	6
30106	2	27	20	208	.1	13	11	956	4.23	12	5	ND	1	41	.6	2	7	80	.55	.065	26	30	.57	122	.07	3	2.53	.01	.05	1	1
30107	1	10	26	132	.1	7	7	325	4.15	8	5	ND	1	16	.3	2	6	71	.18	.077	8	22	.26	60	.07	2	1.71	.01	.03	1	2
30108	1	9	18	87	.2	9	8	350	3.96	10	5	ND	1	15	.2	2	3	69	.18	.086	7	26	.32	50	.10	2	1.98	.01	.04	1	1
30109	2	17	35	94	.6	7	8	520	5.14	10	5	ND	1	25	.2	2	2	70	.20	.091	8	20	.31	109	.09	2	1.96	.01	.06	1	1
30110	2	20	32	85	.3	9	8	465	4.88	8	5	ND	1	17	.2	2	7	75	.15	.115	8	22	.44	62	.11	2	1.98	.01	.03	1	2
30111	1	15	13	90	.2	11	8	1379	3.46	4	5	ND	1	20	.2	2	4	51	.23	.131	7	19	.47	101	.10	4	2.09	.01	.05	1	1
30112	1	8	14	85	.1	9	7	822	3.39	4	5	ND	1	21	.5	2	8	53	.23	.101	7	20	.33	77	.10	2	2.06	.01	.04	2	2
STANDARD C/AU-S	18	57	38	131	6.9	71	31	1051	3.96	42	17	7	38	52	18.4	15	20	56	.51	.096	37	55	.89	181	.07	37	1.88	.06	.14	11	52

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
22636	1	322	48	172	.3	23	24	1123	5.19	2	5	ND	1	62	.2	4	2	82	1.34	.087	8	33	2.67	264	.20	2	3.29	.02	.10	1	5
22637	1	2	8	126	.1	4	4	779	1.99	5	5	ND	1	45	.2	2	2	13	.46	.045	6	6	.65	142	.11	2	1.21	.04	.03	1	3
22639	1	15	14	66	.1	10	7	889	2.70	10	5	ND	1	26	.2	2	2	14	2.12	.040	16	9	.71	83	.01	3	1.39	.02	.19	1	1
22640	1	52	11	118	.3	16	19	1032	5.75	6	5	ND	1	160	.4	6	2	151	1.16	.052	3	29	2.08	327	.15	5	4.76	.35	.91	1	1
22641	1	31	5	73	.2	12	15	687	3.86	2	5	ND	1	365	.3	6	2	121	4.06	.141	4	13	.58	322	.25	6	7.60	.66	.98	1	1
22642	1	44	27	28	.2	19	31	443	7.20	10	5	ND	1	20	.2	2	2	27	2.12	.093	4	8	1.28	40	.01	6	1.58	.03	.21	1	2
22643	6	11	3	5	.1	7	1	39	1.60	9	5	ND	1	69	.2	2	2	1	.03	.019	3	7	.01	245	.01	3	.14	.01	.02	1	1
22644	3	7	226	196	.2	2	1	1555	.90	6	5	ND	11	10	1.0	2	2	3	.63	.029	16	2	.07	38	.03	4	.41	.03	.22	1	1
22645	4	50	12	48	.4	8	8	264	3.50	10	5	ND	2	34	.2	4	2	16	1.12	.065	2	6	.77	74	.03	6	2.59	.15	.64	1	2
22646	1	74	14	61	.1	14	22	308	7.27	7	5	ND	1	88	.3	6	2	35	2.11	.129	3	5	.55	61	.04	3	4.09	.55	.60	1	1
22647	5	62	716	206	243.7	4	1	1762	.72	96	5	ND	1	23	.4	3	30	5	.03	.022	10	5	.02	37	.12	3	.45	.01	.25	10	2010
22648	15	32	13	59	.6	7	22	514	5.13	7	5	ND	1	11	.2	3	3	46	.61	.071	3	6	.72	41	.04	4	1.38	.07	.53	1	1
22649	5	352	293	1013	12.1	5	3	89	5.36	37	5	ND	7	2	13.5	2	8	1	.01	.006	8	4	.01	20	.01	6	.34	.01	.18	1	1
23094	2	1	338	165	3.2	2	1	1199	.59	30	5	ND	3	6	.2	2	2	1	.03	.014	10	2	.01	84	.06	2	.27	.01	.21	2	1
23098	2	13	14	66	.4	6	4	1352	3.84	5	5	ND	1	21	.2	2	2	9	.31	.064	8	6	.43	64	.18	7	1.43	.10	.81	1	1
STANDARD C/AU-R	17	58	38	131	7.2	69	31	1045	3.95	38	23	7	38	52	18.6	15	19	57	.51	.086	38	58	.90	182	.09	33	1.89	.06	.14	11	510

✓ ASSAY RECOMMENDED



LEGEND



-  Fawn 2
Legal corner post, claim boundary and claim name
-  Rock sample location
-  Soil sample location
-  Silt sample location
-  Grid sample location
-  M-262
Sample number
Au (ppb)
-  Contour intervals, ppb

GEOLOGICAL BRANCH
ASSESSMENT REPORT

21,247

SCALE 1:5000
0 200m

PLACER DOME INC.			
PROJECT No. 1381		Omineca M.D.	
Fawn 1-4 Claims			
GEOCHEMICAL RESULTS			
Au (ppb)			
SCALE	DATE	FILE	N.T.S. No.
1:5000	April 89	1381-148	
	26-10-89	BT	93 F/6
	Aug/90	r.n.g.	
			4





- LEGEND**
- Legal Corner flag, claim boundary and claim name
 - Rock sample location
 - Soil sample location
 - Silt sample location
 - Grid sample location
 - Sample number As ppm
 - Contour intervals, ppm
 - 40
 - 25
 - 15
 - 10
 - 5
 - 2

**GEOLOGICAL BRANCH
ASSESSMENT REPORT**

21,247

SCALE 1:5000
0 100 200


PLACER DOME INC.			
PROJECT No 138 I		Omnece M.D.	
Fawn 1-4 Claims GEOCHEMICAL RESULTS As (ppm)			
SCALE	DATE	FILE	NTS No. FIG. No.
1:5000	April 18-91	138-345	
	28-10-89	BY 846	93 F/G
	Aug'90	(GWS)	5





- LEGEND**
- Legal corner post, claim boundary and claim name
 - Rock sample location
 - Soil sample location
 - Silt sample location
 - Grid sample location
 - Sample number Zn ppm
 - Not sampled
 - Topographic elevation in feet
 - Swamp
 - Contour intervals, Zn ppm

GEOLOGICAL BRANCH ASSESSMENT REPORT

21,247



PLACER DOME INC.				
PROJECT NO: 1381		OMINECA M.D.		
Fawn 1-4 Claims				
GEOCHEMICAL RESULTS				
Zn (ppm)				
SCALE	DATE	FILE	NTS	FIG. NO
1:5000	Aug 1990 April 18/91	138-373 By: dip GNG	93 F/G	6



LEGEND

- Fawn 2 Legal corner post, claim boundary and claim name
- Rock sample location
- Soil sample location
- Silt sample location
- Grid sample location
- Sample number Ag ppm
- Not detected
- Contour intervals, ppm

GEOLOGICAL BRANCH ASSESSMENT REPORT

21,247

SCALE 1:5000

PLACER DOME INC.			
PROJECT No. 1381	FILE	NTS. No. Omiteca M. D.	
Fawn 1-4 Claims			
GEOCHEMICAL RESULTS			
Ag (ppm)			
SCALE	DATE	FILE	FIG. No.
1:5000	April 18/91	138-350	7
	27-10-89	BY: r.n.g.	
	Aug. 90		