

Appendix II
Geochemical Analysis and Assay Results
for the
Trenching and Geochemical Program

GEOLOGICAL SURVEY BRANCH
ASSESSMENT REPORT

24,938 ^{3/}/₁₄

CERTIFICATE OF ASSAY AK 96-5031

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

22-Jul-96

ATTENTION: DINO CREMONESE

No. of samples received: 12

Sample type: Rock

PROJECT #: Clone

SHIPMENT #: 1

Samples submitted by: E. Kruchkowski

ET #.	Tag #	Co (%)	Au (g/t)	Au (oz/t)
4	A-96-4	0.049	1.07	0.031
5	A-96-5	0.033	-	-
6	A-96-6	0.030	-	-
7	A-96-7	0.074	5.97	0.174
8	A-96-8	0.064	5.50	0.160
9	A-96-9	0.074	3.03	0.088
10	A-96-10	-	1.22	0.036

QC DATA:

Standard:

SU-1a 0.042 -

AKLS/96TEUTON#1

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

2-Jul-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 96-5031

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 12

Sample type: Rock

PROJECT #: Clone

SHIPMENT #: 1

Samples submitted by: E. Kruchkowski

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	A-96-1	5	<.2	2.24	115	120	<.5	1.47	<.1	12	21	61	4.44	<.10	1.64	711	2	0.04	3	1850	<.2	<.5	<.20	31	0.03	<.10	73	<.10	2	52
2	A-96-2	5	<.2	2.44	235	125	<.5	0.78	<.1	175	30	78	4.28	<.10	1.50	649	3	0.04	3	1940	<.2	<.5	<.20	19	0.02	<.10	55	<.10	1	52
3	A-96-3	75	<.2	2.57	125	145	<.5	1.05	<.1	117	23	41	4.17	<.10	1.62	668	2	0.03	2	1870	<.2	<.5	<.20	21	0.03	<.10	49	<.10	2	62
4	A-96-4	>1000	0.6	1.99	370	215	<.5	1.33	2	458	38	525	4.70	<.10	1.25	793	4	0.02	3	1710	<.2	<.5	<.20	30	0.04	<.10	56	<.10	<.1	139
5	A-96-5	205	0.4	1.97	235	190	<.5	1.58	<.1	299	25	373	3.57	<.10	1.33	960	2	<.01	2	1810	<.2	10	<.20	31	0.03	<.10	46	<.10	3	137
6	A-96-6	200	0.2	1.81	210	135	<.5	2.34	<.1	282	19	274	3.43	<.10	1.17	901	2	<.01	2	1830	<.2	<.5	<.20	43	0.03	<.10	41	<.10	2	101
7	A-96-7	>1000	0.6	1.23	450	125	<.5	0.80	<.1	674	25	520	7.44	<.10	0.77	575	6	<.01	2	1060	<.2	<.5	20	19	0.06	<.10	75	<.10	<.1	89
8	A-96-8	>1000	1.2	1.32	615	465	<.5	0.82	<.1	584	33	1014	7.38	<.10	0.85	540	7	<.01	4	1570	2	<.5	20	23	0.04	<.10	74	<.10	<.1	98
9	A-96-9	>1000	1.6	3.37	705	135	<.5	1.06	<.1	667	29	280	8.96	<.10	2.34	1139	7	0.01	6	1830	<.2	<.5	<.20	24	0.01	<.10	144	<.10	<.1	193
10	A-96-10	>1000	<.2	1.77	85	160	<.5	1.00	<.1	95	30	373	5.55	<.10	1.15	709	4	0.02	3	1670	10	<.5	<.20	22	0.03	<.10	83	<.10	<.1	71
11	A-96-11	5	<.2	3.11	50	125	<.5	0.65	<.1	51	19	183	7.03	<.10	2.49	992	3	0.04	12	1890	<.2	<.5	<.20	13	0.06	<.10	141	<.10	<.1	59
12	A-96-12	5	<.2	1.69	5	85	<.5	0.66	<.1	15	19	44	3.45	<.10	1.15	690	2	0.05	4	1960	<.2	<.5	<.20	13	0.02	<.10	59	<.10	2	39

QC/DATA:

Resplit:

R/S1	A-96-1	5	<.2	2.29	120	125	<.5	1.57	<.1	12	28	61	4.45	<.10	1.65	738	2	0.05	3	1860	<.2	<.5	<.20	33	0.04	<.10	76	<.10	2	51
------	--------	---	-----	------	-----	-----	-----	------	-----	----	----	----	------	------	------	-----	---	------	---	------	-----	-----	------	----	------	------	----	------	---	----

Repeat:

1	A-96-1	-	<.2	2.24	115	120	<.5	1.47	<.1	13	21	61	4.46	<.10	1.65	711	2	0.04	2	1860	<.2	<.5	<.20	31	0.04	<.10	74	<.10	2	52
---	--------	---	-----	------	-----	-----	-----	------	-----	----	----	----	------	------	------	-----	---	------	---	------	-----	-----	------	----	------	------	----	------	---	----

Standard:

GEO'96		150	1.2	1.85	65	160	<.5	1.80	<.1	19	65	82	4.21	<.10	1.00	717	<.1	0.02	20	740	18	<.5	<.20	62	0.12	<.10	81	<.10	4	66
--------	--	-----	-----	------	----	-----	-----	------	-----	----	----	----	------	------	------	-----	-----	------	----	-----	----	-----	------	----	------	------	----	------	---	----

df/S21R
XLS/96Teulon

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AS 96-5051

TEUTON RESOURCES CORPORATION

11-Jul-96

509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 50

Sample type: Rock

PROJECT #: Clone

SHIPMENT #: None given

Samples submitted by: Alex Walus

ET #.	Tag #	Au (g/t)	Au (oz/t)	As (%)
11	D96 - 011	3.70	0.108	-
12	D96 - 012	24.60	0.717	28.88
38	A96 - 034	1.61	0.047	-
39	A96 - 035	1.40	0.041	-
47	A96 - 043	4.30	0.125	-

QC/DATA:

Standard:

CD-1	-	-	1.98
MED	3.17	-	-

XLS/95Teuton

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

CERTIFICATE OF ASSAY AS 96-5051

TEUTON RESOURCES CORPORATION

22-Jul-96

509-675 W. HASTINGS STREET

VANCOUVER, B.C.

V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 50

Sample type: Rock

PROJECT #: Clone

SHIPMENT #: None given

Samples submitted by: Alex Walus

ET #.	Tag #	Co (%)
12	D96 - 012	0.610
33	A96 - 29	0.031

QC/DATA:

Standard:

SU-1a

0.041

CLS/96Teuton#1

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

QC/DATA:

Resplit:

R/S1	D96 - 001	15	18.6	2.19	5	50	<5	1.30	<1	33	145	160	6.67	<10	2.02	503	8	0.04	39	2320	12	<5	<20	40	0.17	<10	192	<10	2	46
R/S36	A96 - 32	20	<.2	1.59	30	95	<5	0.89	<1	14	21	64	4.73	<10	1.02	809	7	0.03	4	2190	16	<5	<20	13	0.03	<10	78	<10	1	54

Repeat:

1	D96 - 001	30	17.2	2.31	10	45	<5	1.32	<1	32	143	156	6.55	<10	2.07	508	8	0.04	36	2440	18	<5	<20	41	0.17	<10	193	<10	2	42
10	D96 - 010	15	1.4	1.34	10	150	<5	0.19	<1	39	150	15	4.57	<10	1.07	661	6	<.01	14	360	6	<5	<20	4	0.02	<10	62	<10	<1	32
19	A96 - 15	10	0.4	2.51	25	105	<5	1.46	<1	35	111	107	6.51	<10	2.24	602	<1	0.07	38	3300	56	<5	<20	75	0.26	<10	211	<10	6	104
36	A96 - 32	20	0.4	1.64	35	100	<5	0.92	<1	15	29	68	4.79	<10	1.02	834	7	0.03	3	2180	16	<5	<20	15	0.04	<10	81	<10	2	55

Standard:

GEO'96	140	1.0	1.72	55	155	<5	1.99	<1	21	67	76	4.06	<10	0.92	783	1	0.01	20	710	20	<5	<20	56	0.10	<10	78	<10	4	72	
GEO'96	135	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

df/5047x
XLS/96Teuton

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5063

TEUTON RESOURCES CORPORATION
509-675 W. Hastings
Vancouver, B.C.
V6C 1N2

22-Jul-96

Attention: Dino Cremonese


No. of samples received: 46
Sample type: Rock
PROJECT #: None Given
SHIPMENT #: None Given
Samples submitted by: Teuton

ET #.	Tag #	Co (%)
21	D96-037	0.029
31	A96-56	0.038

Q/C Data:

Standard:
SU-1a 0.041

XLS/96Teuton#1


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., P.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5063

Teuton Resources Corp.
509-675 W. Hastings
Vancouver, B.C.
V6C 1N2

11-Jul-96

Attention: Dino Cremonese

No. of samples received: 46

Sample type: Rock

PROJECT #: None Given

SHIPMENT #: None Given

Samples submitted by: Teuton

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	As (%)
19	D96-035	2.23	0.065	-	-	-	-
21	D96-037	3.58	0.104	39.0	1.14	1.59	2.48
31	A96-56	6.18	0.180	56.4	1.65	3.09	9.12
34	A96-59	2.70	0.079	-	-	-	-
37	A96-62	1.50	0.044	-	-	-	-
39	A96-64	1.27	0.037	-	-	-	-

Q/C Data:

Standard:

MP1a	-	-	-	-	1.46
CPb-1	-	-	628.0	18.31	-
Std-M	2.85	0.083	-	-	-


ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

11-Jul-98

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS 96-5063

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

Sample received in Kamloops, July 1998

PROJECT #: None Given

SHIPMENT #: 3

P.O.#:

Samples submitted by: Teuton

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	Ln	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	D96-017	<5	<2	1.79	<5	110	<5	1.44	<1	16	98	60	4.18	<10	1.80	639	<1	0.02	33	1120	6	<5	<20	57	0.15	<10	69	<10	8	108
2	D96-018	<5	<2	0.86	<5	<5	<5	5.58	<1	4	173	4	0.96	<10	0.27	982	2	0.01	8	340	2	<5	<20	194	0.05	<10	30	<10	2	27
3	D96-019	<5	0.2	0.77	<5	<5	<5	>15	<1	10	206	34	1.12	<10	1.14	954	<1	<0.01	75	140	<2	10	<20	579	0.03	<10	32	<10	<1	9
4	D96-020	<5	<2	4.17	<5	45	5	3.26	1	41	179	140	7.83	<10	4.16	1210	<1	0.04	94	1830	<2	<5	<20	79	0.23	<10	239	<10	4	66
5	D96-021	<5	<2	1.99	<5	85	10	1.39	1	20	162	47	4.57	<10	2.33	681	<1	0.03	56	1510	6	<5	<20	52	0.34	<10	192	<10	15	176
6	D96-022	<5	<2	1.88	<5	85	5	1.07	1	16	149	66	4.83	<10	1.83	672	3	0.04	38	1300	10	<5	<20	42	0.16	<10	166	<10	10	161
7	D96-023	<5	<2	2.62	<5	50	10	3.97	<1	35	80	83	6.86	<10	2.44	1158	<1	0.04	25	2020	<2	<5	<20	104	0.35	<10	234	<10	8	62
8	D96-024	<5	0.4	1.72	<5	85	<5	0.21	<1	11	78	58	4.09	<10	1.42	262	7	0.02	35	1080	8	<5	<20	15	<0.01	<10	80	<10	2	86
9	D96-025	<5	<2	3.03	<5	105	<5	4.43	1	31	83	102	7.76	<10	3.04	1197	5	0.04	31	2300	<2	<5	<20	124	0.02	<10	268	<10	3	95
10	D96-026	<5	<2	3.01	<5	70	10	1.70	<1	39	48	114	7.13	<10	2.99	856	<1	0.04	20	1610	<2	<5	<20	52	0.32	<10	256	<10	7	65
11	D96-027	<5	<2	3.11	<5	45	5	1.92	<1	32	37	113	7.71	<10	2.73	1150	<1	0.07	18	1490	<2	<5	<20	76	0.27	<10	247	<10	6	68
12	D96-028	<5	<2	5.02	<5	100	20	5.49	2	56	88	71	14.30	<10	5.14	1578	<1	0.01	23	1670	<2	<5	<20	154	0.46	<10	636	<10	6	117
13	D96-029	15	<2	1.83	<5	40	<5	2.55	1	35	67	189	4.68	<10	0.54	375	12	0.03	33	2000	4	<5	<20	36	0.16	<10	89	<10	5	27
14	D96-030	210	0.8	5.09	8660	70	5	0.42	<1	33	241	273	>15	<10	2.71	1002	35	<0.01	25	1630	<2	<5	<20	8	0.07	<10	183	<10	<1	45
15	D96-031	20	2.8	3.29	80	85	<5	0.76	1	98	102	471	>15	<10	2.07	1178	25	<0.01	53	1810	10	<5	<20	12	0.16	<10	145	<10	<1	41
16	D96-032	60	1.6	4.03	285	45	<5	0.49	<1	24	164	1177	10.90	<10	3.12	1165	9	<0.01	15	1140	4	<5	<20	7	0.03	<10	139	<10	<1	48
17	D96-033	60	<2	3.22	40	50	<5	2.92	<1	64	157	422	10.70	<10	1.88	641	14	0.02	62	2370	24	<5	<20	20	0.23	<10	181	<10	1	51
18	D96-034	40	0.4	2.30	40	50	<5	4.17	<1	54	71	277	7.35	<10	0.68	489	7	0.01	63	2190	20	<5	<20	42	0.11	<10	54	<10	1	39
19	D96-035	>1000	2.0	0.52	605	40	10	0.14	<1	44	108	170	10.30	<10	0.19	124	30	<0.01	18	580	12	<5	<20	3	<0.01	20	23	<10	<1	10
20	D96-036	630	1.4	0.14	535	45	10	0.02	<1	26	136	66	12.60	<10	<0.01	21	23	<0.01	20	<10	4	<5	<20	2	<0.01	20	6	<10	<1	7
21	D96-037	>1000	>30	1.65	>10000	90	<5	0.04	<1	276	62	>10000	>15	<10	1.02	395	25	<0.01	34	<10	22	<5	<20	3	0.02	40	114	<10	<1	57
22	A96-47	20	0.6	0.96	75	25	<5	10.10	1	17	143	101	2.97	<10	0.93	1543	6	0.02	43	630	20	<5	<20	338	0.05	<10	141	<10	11	149
23	A96-48	5	<2	1.70	65	45	<5	6.12	<1	25	98	103	4.99	<10	1.45	1059	<1	0.07	35	1790	2	<5	<20	133	0.16	<10	150	<10	4	38
24	A96-49	<5	<2	1.69	5	70	<5	1.88	1	26	80	145	5.74	<10	1.57	814	7	0.04	23	2150	8	<5	<20	55	0.31	<10	199	<10	11	45
25	A96-50	<5	0.6	1.51	<5	90	<5	0.41	1	16	81	65	3.53	<10	1.67	613	<1	0.01	34	980	12	15	<20	29	0.15	<10	51	<10	7	101

07/13/98 11:38 604 573 4557 ECO-TECH LAB.

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	A98- 51	<5	<2	0.75	<5	55	<5	1.10	<1	11	97	32	2.93	<10	0.54	341	<1	0.04	10	650	18	<5	<20	33	0.20	<10	48	<10	12	63
27	A98- 52	5	<2	4.22	<5	60	<5	4.70	2	40	101	299	9.31	<10	2.49	759	2	0.02	38	2140	10	<5	<20	44	0.33	<10	242	<10	<1	37
28	A98- 53	5	<2	3.62	<5	50	10	1.23	<1	37	55	77	7.40	<10	4.08	1099	<1	0.07	25	1870	<2	<5	<20	66	0.31	<10	292	<10	8	81
29	A98- 54	<5	<2	3.23	<5	85	<5	2.12	<1	39	33	104	7.76	<10	2.55	808	<1	0.07	24	1590	2	<5	<20	97	0.31	<10	267	<10	3	71
30	A98- 55	10	<2	2.10	<5	105	<5	1.04	1	26	41	75	7.26	<10	2.24	929	<1	0.03	7	2030	6	<5	<20	34	0.39	<10	299	<10	7	60
31	A98- 56	>1000	>30	0.35	>10000	105	<5	0.03	<1	324	34	>10000	> 15	<10	0.01	25	32	<0.1	21	>10000	<2	<5	80	17	<0.1	30	44	<10	<1	99
32	A98- 57	20	0.2	4.78	170	65	15	0.48	<1	45	99	70	11.90	<10	3.74	2543	7	<0.1	23	1810	<2	<5	<20	11	0.05	<10	173	<10	<1	53
33	A98- 58	85	0.4	0.09	495	30	<5	0.01	<1	10	194	109	4.57	<10	<0.1	83	11	<0.1	6	170	<2	<5	<20	2	<0.1	<10	9	<10	<1	3
34	A98- 59	>1000	8.4	1.04	1080	45	<5	0.06	<1	43	159	984	11.70	<10	0.75	469	15	<0.1	11	<10	4	<5	<20	2	<0.1	10	61	<10	<1	35
35	A98- 60	260	0.4	0.35	340	45	10	0.04	<1	48	165	38	7.99	<10	0.16	257	16	<0.1	9	130	<2	<5	<20	5	<0.1	<10	16	<10	<1	7
36	A98- 61	700	2.8	0.91	105	40	<5	0.13	<1	46	169	63	4.38	<10	0.44	369	20	<0.1	14	590	4	<5	<20	4	<0.1	<10	25	<10	<1	13
37	A98- 62	>1000	0.6	1.29	25	280	<5	1.27	2	28	52	84	5.32	10	0.87	1059	3	<0.1	5	1740	26	<5	<20	37	0.09	<10	97	<10	3	311
38	A98- 63	80	<2	0.95	10	150	<5	2.41	1	10	40	47	3.22	<10	0.49	829	<1	<0.1	3	1930	14	<5	<20	48	0.09	<10	82	<10	4	143
39	A98- 64	>1000	0.2	2.56	5	145	20	1.17	1	56	23	39	12.60	<10	1.87	2287	7	<0.1	2	1690	16	<5	<20	24	0.09	<10	114	<10	<1	257
40	A98- 65	130	0.2	1.52	10	105	5	2.59	<1	20	22	43	4.70	<10	0.89	1222	<1	0.01	3	1950	8	<5	<20	41	0.09	<10	85	<10	2	177
41	A98- 66	25	<2	1.13	<5	15	<5	0.27	<1	12	105	32	3.03	<10	0.89	402	<1	0.04	17	450	<2	<5	<20	8	0.13	<10	82	<10	4	23
42	A98- 67	10	<2	3.34	<5	85	<5	2.32	<1	38	12	180	8.57	<10	2.38	1291	3	0.02	8	2310	<2	<5	<20	55	0.18	<10	273	<10	4	69
43	A98- 68	10	<2	2.68	<5	40	<5	2.22	<1	33	36	281	7.15	<10	1.71	1015	<1	0.04	9	2080	<2	<5	<20	47	0.27	<10	319	<10	5	71
44	A98- 69	15	<2	1.71	<5	65	<5	1.51	9	54	78	228	13.80	<10	0.40	2181	8	<0.1	14	880	24	<5	20	16	0.18	<10	58	<10	<1	615
45	A98- 70	10	<2	3.89	<5	50	5	1.05	1	38	21	136	7.49	<10	3.92	955	<1	0.03	4	2290	<2	<5	<20	24	0.36	<10	347	<10	9	63
46	A98- 71	15	<2	3.02	<5	50	<5	5.24	2	33	11	162	7.38	<10	3.63	1767	2	0.03	3	2250	<2	<5	<20	83	0.27	<10	207	<10	11	83

QC/DATA:

Repeat:																															
RS/1	D98- 017	5	<2	1.78	<5	115	<5	1.44	<1	16	101	61	4.15	<10	1.77	640	<1	0.02	34	1130	4	<5	<20	62	0.16	<10	69	<10	9	107	
RS/36	A98- 61	740	3.0	0.94	110	40	<5	0.13	<1	47	181	62	4.61	<10	0.46	368	20	<0.1	17	580	4	<5	<20	4	<0.1	<10	27	<10	<1	13	
Repeat:																															
1	D98- 017	<5	0.2	1.80	<5	110	<5	1.47	<1	16	101	59	4.23	<10	1.79	646	<1	0.02	33	1140	8	<5	<20	56	0.17	<10	70	<10	8	110	
10	D98- 026	<5	<2	3.02	<5	70	5	1.72	<1	39	48	114	7.04	<10	2.99	856	<1	0.04	20	1800	<2	<5	<20	52	0.34	<10	258	<10	8	63	
19	D98- 035	>1000	2.0	0.54	610	50	<5	0.15	<1	45	114	165	10.70	<10	0.19	128	32	<0.1	23	540	10	<5	<20	5	<0.1	10	24	<10	<1	10	
36	A98- 61	700	3.0	0.91	100	40	<5	0.13	<1	46	168	62	4.37	<10	0.44	368	20	<0.1	13	590	4	<5	<20	3	<0.1	<10	25	<10	<1	13	
45	A98- 70	-	<2	3.70	<5	45	10	1.05	<1	38	21	138	7.42	<10	3.94	950	<1	0.03	5	2280	<2	<5	<20	24	0.36	<10	348	<10	9	62	
Standard:																															
GEO'98		140	1.2	2.00	60	165	<5	2.05	<1	21	73	82	4.02	<10	1.07	781	<1	0.02	20	710	20	<5	<20	71	0.16	<10	80	<10	5	76	

d95063r
XLS/95Teuton


ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

003

ECO-TECH KAM.

0604 573 4337

11:37

07/12/98



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5072

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

22-Jul-96

ATTENTION: DINO CREMONESE

No. of samples received: 73

PROJECT #: Clone

SHIPMENT #: None given

Samples submitted by: Not indicated

ET #.	Tag #	Au (g/t)	Au (oz/t)	As (%)	Co (%)
12	D-96-049	3.91	0.114		
13	D-96-050	19.09	0.557	-	-
14	D-96-051	12.71	0.371	-	-
15	D-96-052	21.84	0.637	-	-
16	D-96-053	13.69	0.399	-	-
17	D-96-054	12.38	0.361	-	-
18	D-96-055	16.63	0.485	-	-
19	D-96-056	1.69	0.049	-	-
20	D-96-057	28.60	0.834	-	-
21	D-96-058	9.99	0.291	-	-
22	D-96-059	6.22	0.181	-	-
23	D-96-060	7.10	0.207	-	-
27	D-96-064	1.72	0.050	1.14	-
53	D-96-093	1.75	0.051	2.88	-
64	D-96-104	16.95	0.494	6.10	0.420

A-96-093
A-96-104

QC/DATA:

Standard:

STD-M	3.26	0.095	-	-
CD-1	-	-	0.66	-
Sula	-	-	-	0.041

ECO-TECH LABORATORIES LTD.

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 8T4

ICP CERTIFICATE OF ANALYSIS - AS-5072

TEUTON RESOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V8C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 73
PROJECT #: Clone
SHIPMENT #: None given
Samples submitted by: Not indicated

Values in ppm unless otherwise reported

Et#.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	D-98-038	5	<0.2	1.44	<5	20	<5	1.73	<1	21	118	54	2.32	<10	0.91	530	<1	0.03	9	1760	20	<5	<20	22	0.19	<10	101	<10	5	28
2	D-98-039	5	<0.2	1.22	<5	30	<5	3.37	<1	13	104	8	3.30	<10	0.68	913	2	0.03	9	860	<2	<5	<20	77	0.06	<10	129	<10	<1	23
3	D-98-040	5	<0.2	0.56	<5	10	<5	1.65	<1	7	123	11	1.43	<10	0.48	348	2	<0.01	5	410	<2	<5	<20	30	0.04	<10	50	<10	<1	12
4	D-98-041	5	<0.2	3.32	<5	60	5	0.59	2	31	23	83	8.86	<10	3.70	1524	2	0.02	11	2160	<2	<5	<20	14	0.16	<10	336	<10	<1	61
5	D-98-042	5	<0.2	3.32	<5	40	<5	1.08	15	45	25	154	>10	<10	3.25	1562	3	0.02	12	2040	2	<5	<20	22	0.21	<10	296	<10	<1	975
6	D-98-043	5	<0.2	2.41	<5	35	<5	1.95	1	49	31	209	8.32	<10	2.16	1224	<1	0.03	13	2060	<2	<5	<20	21	0.25	<10	275	<10	4	91
7	D-98-044	5	<0.2	1.50	<5	35	<5	0.91	5	31	23	138	6.67	<10	1.33	589	2	0.03	8	2230	74	<5	<20	14	0.20	<10	229	<10	3	212
8	D-98-045	190	3.0	0.21	445	50	<5	2.82	<1	64	97	61	7.45	<10	0.69	1059	11	<0.01	14	590	36	<5	<20	85	<0.01	<10	14	<10	<1	23
9	D-98-046	135	4.8	2.11	270	60	<5	0.90	<1	103	62	691	>10	<10	1.37	464	18	<0.01	52	70	46	<5	<20	9	0.02	30	114	<10	<1	26
10	D-98-047	690	11.4	0.71	1525	50	5	1.06	<1	85	31	86	>10	<10	0.30	451	16	<0.01	59	620	106	<5	<20	13	<0.01	20	28	<10	<1	41
11	D-98-048	795	9.8	1.00	1725	50	15	1.01	<1	82	57	44	>10	<10	0.39	479	16	<0.01	64	490	112	<5	<20	11	<0.01	20	28	<10	<1	22
12	D-98-049	>1000	2.8	0.48	1480	45	15	1.03	<1	127	75	182	>10	<10	0.20	216	13	<0.01	8	220	6	<5	<20	11	<0.01	10	9	<10	<1	16
13	D-98-050	>1000	3.4	0.10	1830	40	<5	0.06	<1	61	88	274	>10	<10	<0.01	60	15	<0.01	5	<10	12	<5	<20	2	<0.01	30	3	<10	<1	15
14	D-98-051	>1000	2.4	0.39	1930	50	<5	0.63	<1	89	66	296	>10	<10	0.18	205	14	<0.01	4	<10	6	<5	<20	9	<0.01	20	7	<10	<1	14
15	D-98-052	>1000	6.6	0.29	1330	45	<5	3.34	<1	80	71	1949	>10	<10	0.10	511	10	<0.01	6	<10	16	<5	<20	35	<0.01	<10	5	<10	<1	12
16	D-98-053	>1000	3.0	0.06	1925	40	<5	0.32	<1	76	70	361	>10	<10	<0.01	68	15	<0.01	4	<10	10	<5	<20	4	<0.01	30	2	<10	<1	9
17	D-98-054	>1000	5.0	0.73	1660	45	<5	>10	<1	88	51	1478	>10	<10	0.49	2202	15	<0.01	16	<10	18	<5	<20	158	<0.01	<10	11	<10	<1	24
18	D-98-055	>1000	4.2	0.33	2495	115	<5	0.35	<1	53	55	483	>10	<10	<0.01	189	78	<0.01	11	750	6	<5	<20	8	<0.01	40	19	<10	<1	31
19	D-98-056	>1000	8.4	0.84	1640	50	40	0.49	<1	86	43	89	>10	<10	0.20	316	20	<0.01	77	570	74	<5	<20	7	<0.01	20	18	<10	<1	16
20	D-98-057	>1000	16.0	0.06	1465	45	<5	0.04	<1	96	70	1792	>10	<10	<0.01	4	25	<0.01	9	<10	12	<5	<20	1	<0.01	30	3	<10	<1	14
21	D-98-058	>1000	5.4	0.63	600	50	<5	3.67	<1	46	94	1831	>10	<10	0.39	456	9	<0.01	33	2050	4	<5	<20	45	<0.01	<10	25	<10	<1	16
22	D-98-059	>1000	4.4	0.53	1840	45	<5	0.14	<1	18	85	234	>10	<10	0.17	113	17	<0.01	36	380	16	<5	<20	4	<0.01	20	21	<10	<1	18
23	D-98-060	>1000	7.0	0.10	1170	40	<5	0.02	<1	29	82	464	>10	<10	<0.01	6	17	<0.01	8	<10	2	<5	<20	1	<0.01	20	3	<10	<1	12
24	D-98-061	585	1.2	1.43	75	45	<5	1.40	<1	58	91	182	>10	<10	0.66	539	7	0.03	52	2490	34	<5	<20	27	0.10	<10	84	<10	<1	40
25	D-98-062	145	0.6	1.66	5	55	<5	2.60	<1	49	72	169	7.64	<10	0.71	419	5	0.02	46	2850	46	<5	<20	16	0.12	<10	76	<10	<1	61

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS-5072

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	D-96-063	95	<0.2	1.95	30	35	<5	2.42	<1	39	107	123	9.87	<10	2.00	638	5	0.02	32	2160	44	<5	<20	27	0.19	<10	249	<10	<1	84
27	D-96-064	>1000	4.8	0.29	10000	40	<5	1.11	<1	48	96	295	>10	<10	0.08	308	18	<0.01	14	320	376	<5	<20	41	<0.01	<10	12	<10	<1	21
28	D-96-065	195	0.2	1.62	230	50	<5	0.52	<1	81	42	238	>10	<10	0.98	569	30	0.02	43	1420	16	<5	<20	21	0.09	<10	104	<10	<1	36
29	D-96-066	405	8.0	0.61	185	40	<5	0.34	<1	17	89	239	>10	<10	0.31	267	15	<0.01	14	550	96	<5	<20	5	<0.01	<10	14	<10	<1	137
30	D-96-067	225	5.8	2.81	650	55	<5	0.77	<1	32	130	5825	8.80	<10	1.98	1542	8	<0.01	39	2630	12	<5	<20	15	0.01	<10	138	<10	<1	89
31	D-96-068	165	0.6	0.43	605	20	<5	5.16	<1	30	94	186	5.27	<10	0.30	874	4	<0.01	15	890	10	<5	<20	45	0.06	<10	22	<10	<1	16
32	D-96-072	10	0.8	1.87	15	25	<5	3.22	<1	38	51	115	7.59	<10	0.77	414	5	0.14	39	2130	30	<5	<20	109	0.09	<10	59	<10	<1	36
33	D-96-073	25	0.8	1.42	15	40	<5	2.22	<1	66	93	334	>10	<10	0.95	496	9	0.01	83	2120	40	<5	<20	24	0.09	<10	104	<10	<1	40
34	D-96-074	15	0.4	2.54	10	25	<5	3.14	<1	26	34	124	6.20	<10	0.54	429	3	0.17	23	3610	28	<5	<20	175	0.09	<10	56	<10	2	43
35	D-96-075	5	<0.2	1.25	<5	30	<5	2.15	<1	38	92	87	6.19	<10	0.75	400	2	0.02	37	2290	20	<5	<20	27	0.17	<10	89	<10	2	41
36	D-96-076	20	0.4	2.64	5	35	<5	1.94	<1	48	79	283	7.98	<10	1.45	673	2	0.21	39	1490	8	<5	<20	155	0.20	<10	102	<10	<1	29
37	D-96-077	155	<0.2	1.51	45	30	<5	1.66	<1	35	77	115	6.15	<10	1.25	382	6	0.04	34	1780	8	<5	<20	34	0.22	<10	130	<10	3	28
38	D-96-078	75	<0.2	1.98	15	25	<5	2.18	<1	31	90	121	6.33	<10	1.52	516	3	0.03	30	1780	10	<5	<20	30	0.22	<10	149	<10	2	48
39	D-96-079	10	<0.2	1.97	<5	30	<5	1.79	<1	35	55	164	6.87	<10	1.57	541	1	0.09	24	2780	6	<5	<20	77	0.19	<10	158	<10	4	48
40	D-96-080	25	<0.2	1.65	<5	45	<5	1.18	<1	48	82	256	8.79	<10	1.42	525	2	0.07	39	2080	4	<5	<20	53	0.21	<10	137	<10	1	27
41	D-96-081	10	<0.2	2.18	25	35	<5	1.90	<1	36	59	191	6.78	<10	1.98	675	11	0.05	23	2690	6	<5	<20	61	0.20	<10	177	<10	4	40
42	D-96-082	5	<0.2	1.63	<5	35	<5	2.39	<1	33	58	121	5.55	<10	1.65	503	<1	0.04	24	2710	8	<5	<20	60	0.22	<10	165	<10	4	39
43	D-96-083	10	<0.2	1.77	<5	30	<5	2.04	<1	37	74	176	5.76	<10	1.39	447	12	0.08	33	2360	4	<5	<20	80	0.22	<10	132	<10	3	30
44	D-96-084	15	<0.2	2.04	<5	30	<5	2.00	<1	47	97	170	8.12	<10	1.25	549	5	0.07	64	2760	2	<5	<20	63	0.17	<10	125	<10	<1	45
45	D-96-085	5	<0.2	2.34	<5	40	<5	2.21	2	38	74	138	7.12	<10	0.95	442	2	0.19	51	2760	10	<5	<20	142	0.16	<10	88	<10	1	90
46	D-96-086	5	<0.2	2.06	<5	40	<5	2.55	<1	37	121	133	6.00	<10	1.31	349	<1	0.03	53	2700	6	<5	<20	32	0.22	<10	127	<10	3	32
47	D-96-087	5	<0.2	1.20	20	30	<5	2.83	<1	26	56	120	4.99	<10	0.64	434	3	0.03	23	1890	8	<5	<20	62	0.14	<10	116	<10	4	28
48	D-96-088	5	<0.2	1.47	<5	30	<5	1.74	<1	24	42	101	4.95	<10	0.77	348	2	0.04	20	1970	12	<5	<20	49	0.15	<10	97	<10	3	27
49	D-96-089	5	<0.2	2.70	30	25	<5	2.38	<1	36	71	119	4.97	<10	0.82	343	20	0.26	40	1850	26	<5	<20	197	0.18	<10	78	<10	2	30
50	D-96-090	5	<0.2	2.45	35	35	<5	1.98	<1	38	137	122	5.55	<10	1.55	447	<1	0.13	51	1840	8	<5	<20	96	0.22	<10	142	<10	<1	42
51	D-96-091	5	<0.2	2.13	10	25	<5	3.14	<1	29	54	161	4.98	<10	0.59	321	3	0.02	21	1940	24	<5	<20	27	0.14	<10	77	<10	2	34
52	D-96-092	5	<0.2	2.63	80	65	<5	4.88	<1	25	134	118	5.92	<10	2.42	1056	4	0.02	34	1680	18	<5	<20	269	0.06	<10	210	<10	3	91
53	D-96-093	>1000	<0.2	0.35	10000	40	10	2.29	<1	153	103	29	4.88	<10	0.19	439	5	<0.01	45	300	4	30	<20	38	<0.01	<10	21	<10	<1	11
54	D-96-094	5	<0.2	3.95	190	35	<5	3.00	<1	20	42	66	5.52	<10	2.69	995	<1	0.03	6	1310	<2	<5	<20	21	0.27	<10	166	<10	7	70
55	D-96-095	5	<0.2	2.78	95	55	<5	2.74	<1	30	57	140	4.94	<10	0.47	339	2	0.19	29	2140	<2	<5	<20	113	0.13	<10	61	<10	2	30
56	D-96-096	5	0.2	1.52	25	40	<5	2.05	<1	39	78	160	6.01	<10	0.61	254	1	0.13	42	1970	8	<5	<20	79	0.16	<10	102	<10	3	40
57	D-96-097	5	1.0	2.13	40	35	<5	2.35	<1	29	42	171	6.57	<10	1.00	755	2	0.04	21	1650	<2	<5	<20	38	0.12	<10	113	<10	<1	80
58	D-96-098	5	<0.2	1.59	20	30	<5	1.68	<1	26	45	149	5.29	<10	1.03	368	7	0.03	22	1840	4	<5	<20	31	0.16	<10	134	<10	2	29
59	D-96-099	230	1.0	0.70	3535	<5	<5	>10	<1	21	50	99	4.25	<10	0.91	4405	4	<0.01	4	130	<2	<5	<20	419	0.02	<10	28	<10	4	9
60	D-96-100	20	0.6	0.43	625	45	<5	>10	<1	12	84	395	6.29	<10	0.44	2461	8	<0.01	6	200	<2	<5	<20	169	<0.01	<10	19	<10	<1	11

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
61	D-96-101	5	<0.2	2.04	20	40	<5	2.49	<1	33	116	129	5.28	<10	1.28	360	<1	0.05	44	2580	<2	<5	<20	74	0.24	<10	159	<10	5	36
62	D-96-102	5	<0.2	5.67	25	40	5	2.87	<1	28	20	75	>10	<10	5.15	1113	7	0.01	14	1970	<2	<5	<20	71	0.04	<10	383	<10	<1	57
63	D-96-103	320	<0.2	4.37	575	50	<5	1.77	<1	119	39	441	>10	<10	3.98	1150	16	<0.01	7	1620	<2	<5	<20	39	0.03	<10	316	<10	<1	50
64	D-96-104	>1000	2.8	4.34	10000	70	<5	0.37	<1	3451	31	983	>10	<10	3.89	887	134	<0.01	4	940	4	<5	<20	62	0.03	<10	238	<10	<1	48
65	D-96-105	120	<0.2	4.58	515	40	<5	3.22	<1	78	15	38	7.83	<10	4.54	970	5	0.02	13	2020	<2	<5	<20	88	0.04	<10	321	<10	1	49
66	D-96-106	255	<0.2	5.33	200	45	<5	3.85	<1	168	35	141	9.35	<10	5.83	1145	4	0.01	16	1630	<2	<5	<20	90	0.11	<10	337	<10	2	46
67	D-96-107	5	<0.2	4.28	40	30	<5	5.65	<1	32	13	160	7.79	<10	4.28	1048	2	0.02	12	1790	<2	<5	<20	135	0.16	<10	275	<10	4	40
68	D-96-108	70	<0.2	3.20	120	50	<5	3.98	<1	37	25	222	7.30	<10	2.90	1014	<1	0.02	7	2490	<2	<5	<20	73	0.25	<10	288	<10	4	47
69	D-96-109	110	<0.2	3.85	165	55	<5	2.24	<1	38	16	433	8.88	<10	3.78	1119	2	0.03	8	2440	<2	<5	<20	47	0.24	<10	324	<10	2	49
70	D-96-110	65	<0.2	4.31	55	50	<5	3.11	<1	33	48	144	8.89	<10	4.29	1338	<1	0.04	15	2180	<2	<5	<20	55	0.27	<10	302	<10	1	55
71	D-96-111	540	<0.2	3.96	110	40	<5	2.72	<1	42	23	257	9.06	<10	3.88	1239	5	0.03	14	2280	<2	<5	<20	51	0.21	<10	287	<10	<1	49
72	D-96-112	40	<0.2	4.38	90	65	<5	1.45	<1	35	19	164	9.47	<10	4.19	1409	2	0.03	12	2390	<2	<5	<20	38	0.24	<10	316	<10	<1	56
73	D-96-113	120	<0.2	4.27	175	70	<5	2.01	<1	39	21	268	9.91	<10	3.99	1254	5	0.04	11	2300	<2	<5	<20	46	0.24	<10	353	<10	<1	46

QC/DATA:

Resplit:

R/S 1	D-96-038		<0.2	1.33	<5	20	<5	1.88	<1	25	106	47	2.56	<10	0.83	566	<1	0.02	11	1820	18	<5	<20	19	0.22	<10	101	<10	4	32
R/S 36	D-96-076		0.2	2.64	10	35	<5	1.88	<1	51	72	271	7.91	<10	1.41	656	3	0.22	42	1480	4	<5	<20	158	0.18	<10	96	<10	<1	27

Repeat:

1	D-96-038	5	<0.2	1.42	<5	20	<5	1.77	<1	22	117	53	2.34	<10	0.89	533	<1	0.03	9	1760	18	<5	<20	22	0.20	<10	101	<10	5	24
10	D-96-047	700	11.8	0.68	1840	50	15	1.17	<1	95	32	78	>10	<10	0.23	470	17	<0.01	63	730	120	<5	<20	10	<0.01	20	27	<10	<1	52
19	D-96-056	>1000	8.4	0.87	1625	50	40	0.49	<1	87	43	92	>10	<10	0.21	316	19	<0.01	78	590	70	<5	<20	7	<0.01	20	18	<10	<1	17
36	D-96-076	20	0.4	2.67	10	35	<5	1.98	<1	46	80	260	7.41	<10	1.46	681	1	0.21	36	1510	8	<5	<20	157	0.20	<10	104	<10	1	30
45	D-96-085	5	<0.2	2.39	<5	35	<5	2.01	<1	32	68	149	7.07	<10	0.99	411	2	0.22	42	2620	8	<5	<20	150	0.15	<10	87	<10	2	70
54	D-96-094	-	<0.2	3.93	190	35	<5	3.16	<1	22	44	63	5.82	<10	2.65	1036	<1	0.03	5	1420	<2	<5	<20	21	0.28	<10	168	<10	7	79
61	D-96-101	5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

Standard:

GEO96		150	1.4	1.73	65	165	<5	1.90	<1	23	74	73	4.02	<10	0.94	710	<1	0.01	22	720	20	<5	<20	51	0.14	<10	85	<10	4	72
GEO96		150	1.0	1.96	65	160	<5	1.84	1	19	66	85	4.23	<10	1.03	722	3	0.02	22	680	18	15	<20	60	0.11	<10	87	<10	4	72

df9072R/5071R
XLS/96Teuton

per 
 BCO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5079

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

22-Jul-96

ATTENTION: DINO CREMONESE

No. of samples received: 57
PROJECT #: Clone
SHIPMENT #: 7
Samples submitted by: A. Raven

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	As (%)	Cu (%)	Co (%)
87	7 A-96-120	-	-	-	-	-	-	0.020
7	21 A-96-134	-	-	73.4	2.141	1.61	0.96	-
7	22 A-96-135	-	-	38.5	1.123	-	-	-
91	31 A-96-144	33.11	0.966	-	-	-	-	-
91	34 A-96-147	1.26	0.037	-	-	-	-	0.026
92	42 A-96-155	4.80	0.140	-	-	-	-	-
92	43 A-96-156	1.91	0.056	-	-	-	-	-
93	45 A-96-158	32.52	0.948	-	-	1.05	-	0.069
93	46 A-96-159	1.87	0.055	-	-	-	-	-
94	51 A-96-164	4.82	0.141	-	-	-	-	-
95	53 A-96-166	134.22	3.914	103.6	3.021	21.83	-	1.16
95	54 A-96-167	11.96	0.349	-	-	1.33	-	0.082

QC/DATA:

Standard:

CPb-1	-	-	632.0	18.431	-	-	-	-
CD-1	-	-	-	-	0.66	-	-	-
Sula	-	-	-	-	-	0.96	0.041	-

XLS/96Teuton#2


ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 96-5079

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 58
PROJECT #: Clonie
SHIPMENT #: 7
Samples submitted by: A. Raven

Values in ppm unless otherwise reported

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Ni %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	A-96-114	30	<0.2	2.41	10	80	5	1.77	<1	18	35	66	5.69	<10	1.83	976	<1	0.02	7	2110	6	<5	<20	33	0.14	<10	79	<10	3	53
2	A-96-115	120	<0.2	2.34	15	75	<5	2.01	1	25	28	197	6.64	<10	1.84	994	<1	0.02	6	2180	6	<5	<20	31	0.14	<10	100	<10	2	44
3	A-96-116	10	0.6	2.45	35	90	<5	2.01	2	186	22	876	7.12	<10	1.98	1083	<1	0.01	9	2000	6	<5	<20	41	0.15	<10	113	<10	1	119
4	A-96-117	65	<0.2	1.69	10	130	<5	1.63	<1	20	23	73	4.41	<10	1.35	664	1	0.02	3	1870	4	<5	<20	77	0.09	<10	63	<10	2	41
5	A-96-118	50	<0.2	2.41	40	130	<5	2.33	3	130	29	456	7.58	<10	1.93	686	2	0.02	9	2140	24	<5	<20	43	0.15	<10	146	<10	2	71
6	A-96-119	235	<0.2	1.72	5	120	<5	1.21	1	13	31	76	3.27	<10	0.97	571	<1	0.03	3	1880	8	<5	<20	99	0.11	<10	51	<10	3	31
7	A-96-120	50	0.4	1.63	30	90	<5	1.84	<1	214	30	186	4.13	<10	1.27	757	2	0.01	4	1800	6	<5	<20	33	0.07	<10	69	<10	3	148
8	A-96-121	35	<0.2	1.95	<5	90	<5	1.01	2	78	24	303	4.49	<10	1.41	787	<1	0.02	3	1900	6	<5	<20	19	0.10	<10	70	<10	3	68
9	A-96-122	80	<0.2	3.84	15	85	<5	2.19	1	65	26	154	>10	<10	3.42	1561	3	0.02	18	2260	6	<5	<20	39	0.17	<10	198	<10	<1	98
10	A-96-123	50	<0.2	2.42	<5	70	<5	4.17	2	32	26	200	6.66	<10	2.11	1094	<1	0.02	10	1960	4	<5	<20	62	0.18	<10	140	<10	3	45
11	A-96-124	15	<0.2	1.75	15	120	<5	2.37	1	88	28	127	5.78	<10	1.26	736	1	0.03	8	1960	10	<5	<20	52	0.12	<10	111	<10	1	64
12	A-96-125	220	<0.2	1.82	30	90	<5	4.25	2	77	28	135	4.50	<10	1.27	914	<1	0.02	5	1950	10	<5	<20	62	0.12	<10	93	<10	2	81
13	A-96-126	75	<0.2	1.69	<5	80	<5	3.61	1	26	24	102	4.41	<10	1.16	845	2	0.03	5	2030	8	<5	<20	62	0.10	<10	81	<10	1	39
14	A-96-127	10	5.2	1.97	75	70	<5	0.56	6	34	31	5692	4.81	<10	1.39	582	382	0.02	6	1990	6190	<5	<20	11	0.03	<10	80	<10	<1	73
15	A-96-128	30	<0.2	2.36	50	95	<5	0.61	<1	65	21	334	4.29	<10	1.65	771	4	0.02	4	2050	54	<5	<20	16	0.04	<10	60	<10	2	124
16	A-96-129	35	<0.2	2.32	30	90	<5	0.62	<1	59	26	293	4.06	<10	1.61	732	2	0.02	4	2080	30	<5	<20	11	0.04	<10	59	<10	2	116
17	A-96-130	310	<0.2	2.18	5	115	<5	1.07	1	22	18	50	5.34	<10	1.56	921	3	0.01	4	1950	16	<5	<20	22	0.07	<10	65	<10	2	235
18	A-96-131	150	<0.2	1.77	25	100	5	1.50	<1	83	29	37	5.26	<10	1.34	893	2	0.01	2	1900	10	<5	<20	31	0.06	<10	93	<10	<1	135
19	A-96-132	90	<0.2	1.79	70	100	<5	0.82	<1	74	28	96	4.27	<10	1.26	780	4	0.01	5	1830	22	<5	<20	17	0.06	<10	68	<10	3	78
20	A-96-133	45	<0.2	1.99	60	90	<5	1.07	<1	65	40	107	4.30	<10	1.41	765	2	0.03	7	1840	20	<5	<20	34	0.10	<10	84	<10	3	74
21	A-96-134	20	>30	1.16	>10000	50	<5	2.31	<1	41	58	10000	9.47	<10	0.92	500	5	0.03	20	1040	14	185	<20	55	0.10	<10	82	<10	<1	52
22	A-96-135	505	>30	2.32	9170	50	<5	2.29	<1	45	85	6738	7.80	<10	1.55	629	3	0.07	31	1470	12	95	<20	102	0.17	<10	126	<10	<1	73
23	A-96-136	465	<0.2	2.55	95	105	<5	1.66	<1	17	55	188	5.22	<10	2.07	548	<1	0.06	5	2100	8	<5	<20	76	0.35	<10	219	<10	6	29
24	A-96-137	30	<0.2	2.46	35	30	<5	2.12	<1	33	58	185	5.23	<10	1.82	436	<1	0.03	23	2390	12	<5	<20	41	0.19	<10	155	<10	3	25
25	A-96-138	200	0.8	0.69	20	<5	<5	>10	<1	5	8	28	1.18	10	0.71	4072	<1	<0.01	2	270	<2	10	<20	432	0.03	<10	30	<10	11	11

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
26	A-96-139	290	0.8	1.64	35	20	<5	>10	<1	12	18	31	3.04	10	1.65	4120	<1	<0.01	4	610	<2	15	<20	409	0.06	<10	48	<10	7	19
27	A-96-140	60	<0.2	2.97	65	35	5	1.03	<1	42	87	83	8.62	<10	3.01	1346	5	0.03	20	1870	26	<5	<20	18	0.13	<10	256	<10	<1	47
28	A-96-141	5	1.4	0.66	<5	20	<5	0.32	<1	8	172	128	1.45	<10	0.55	268	3	<0.01	4	370	2088	<5	<20	8	0.02	<10	26	<10	<1	23
29	A-96-142	255	0.8	2.48	220	90	<5	0.45	<1	28	35	416	4.99	<10	1.69	934	3	0.01	4	1910	18	<5	<20	9	0.02	<10	81	<10	2	188
30	A-96-143	40	4.8	0.77	45	55	<5	0.39	1	15	141	56	4.57	<10	0.25	102	61	<0.01	77	1850	60	15	<20	13	<0.01	<10	160	<10	2	233
31	A-96-144	>1000	15.2	1.24	370	135	<5	0.16	<1	140	42	845	>10	<10	0.86	649	35	<0.01	8	130	18	<5	<20	7	0.03	50	111	<10	<1	318
32	A-96-145	280	0.2	2.09	40	75	<5	0.88	<1	23	36	137	4.75	<10	1.54	763	5	0.02	3	1920	10	<5	<20	15	0.03	<10	73	<10	1	179
33	A-96-146	155	<0.2	2.08	105	70	<5	0.34	<1	110	42	134	4.68	<10	1.41	956	3	0.01	4	1270	10	<5	<20	6	0.04	<10	71	<10	4	183
34	A-96-147	>1000	0.6	4.21	715	80	<5	0.48	<1	270	51	410	>10	<10	3.28	1121	6	<0.01	11	1660	16	<5	<20	8	0.11	<10	161	<10	<1	231
35	A-96-148	80	<0.2	4.05	110	90	<5	0.54	2	43	19	184	8.78	<10	3.24	1033	7	0.01	14	2280	12	<5	<20	12	0.02	<10	170	<10	<1	133
38	A-96-149	25	<0.2	2.17	40	80	<5	1.01	<1	20	17	40	4.37	<10	1.60	680	2	0.03	3	1880	4	<5	<20	18	0.03	<10	71	<10	1	53
37	A-96-150	100	<0.2	1.74	40	65	<5	2.44	<1	36	25	36	4.00	<10	1.35	586	1	0.03	3	1920	6	<5	<20	41	0.06	<10	83	<10	4	48
38	A-96-151	430	<0.2	4.05	155	95	<5	1.95	<1	158	40	153	9.40	<10	3.53	1594	2	0.02	18	2180	<2	<5	<20	35	0.22	<10	190	<10	3	88
39	A-96-152	130	<0.2	4.02	135	85	<5	2.86	<1	123	21	373	>10	<10	3.40	1652	3	0.02	15	2210	4	<5	<20	50	0.24	<10	226	<10	<1	87
40	A-96-153	75	<0.2	3.06	70	70	<5	3.07	<1	30	20	163	7.14	<10	2.42	1131	2	0.03	8	2570	12	<5	<20	54	0.19	<10	178	<10	4	65
41	A-96-154	150	0.8	2.06	275	90	<5	1.07	<1	58	19	866	5.10	<10	1.21	816	5	0.01	4	1750	8	<5	<20	16	0.02	<10	60	<10	<1	183
42	A-96-155	>1000	6.0	3.70	2025	85	<5	0.37	<1	82	36	5196	>10	<10	2.38	1490	25	<0.01	3	1410	4	<5	<20	4	0.01	<10	125	<10	<1	436
43	A-96-156	>1000	2.2	2.53	260	100	<5	0.46	3	61	28	1257	6.85	<10	1.78	1564	11	<0.01	4	1670	4	<5	<20	5	0.02	<10	68	<10	1	321
44	A-96-157	685	0.6	2.83	270	105	<5	0.52	<1	88	22	426	6.62	<10	2.05	1049	7	<0.01	5	1810	6	<5	<20	7	0.06	<10	87	<10	<1	176
45	A-96-158	>1000	16.0	3.65	>10000	55	<5	2.67	<1	661	24	1144	>10	<10	2.41	935	356	<0.01	6	1500	276	<5	<20	41	0.04	<10	190	<10	<1	857
46	A-96-159	>1000	2.4	3.58	245	45	<5	4.97	1	30	21	506	>10	<10	3.13	1284	61	0.02	9	2490	90	<5	<20	72	0.12	<10	264	<10	<1	220
47	A-96-160	185	<0.2	3.78	100	35	<5	5.13	<1	20	23	182	8.80	<10	3.31	1356	11	0.03	7	2710	22	<5	<20	78	0.17	<10	287	<10	2	85
48	A-96-161	105	0.2	2.76	745	70	<5	0.91	<1	29	13	133	5.94	<10	1.54	974	5	<0.01	6	2220	64	<5	<20	27	0.09	<10	76	<10	4	191
49	A-96-162	55	0.4	3.25	85	55	<5	3.57	1	31	14	147	6.52	<10	1.95	1495	3	<0.01	7	2910	98	<5	<20	80	0.11	<10	100	<10	6	194
50	A-96-163	40	<0.2	3.82	100	75	<5	0.87	<1	33	13	166	7.78	<10	2.26	1293	4	<0.01	7	3250	12	<5	<20	36	0.10	<10	109	<10	5	96
51	A-96-164	>1000	1.2	2.23	1535	50	<5	1.48	<1	171	21	224	6.94	<10	1.73	1046	12	0.02	8	1120	26	<5	<20	20	0.10	<10	83	<10	<1	54
52	A-96-165	95	<0.2	4.29	70	35	<5	4.13	<1	55	30	172	8.43	<10	4.11	1410	7	0.02	9	2720	12	<5	<20	72	0.19	<10	293	<10	3	143
53	A-96-166	>1000	>30	0.88	>10000	60	<5	0.09	<1	10000	<1	2423	>10	<10	0.36	192	216	<0.01	<1	<10	3176	135	<20	11	<0.01	50	40	<10	<1	3383
54	A-96-167	>1000	7.6	5.18	>10000	60	<5	0.53	<1	800	21	952	>10	<10	3.28	1069	66	<0.01	3	2070	242	<5	<20	9	0.08	<10	311	<10	<1	304
55	A-96-168	630	<0.2	4.72	1005	60	<5	3.62	<1	97	32	362	>10	<10	4.17	1216	14	0.02	16	2240	28	<5	<20	75	0.19	<10	323	<10	<1	82
56	A-96-169	445	1.0	4.11	395	55	<5	2.45	<1	80	30	933	>10	<10	3.11	1130	16	<0.01	24	2010	32	<5	<20	38	0.14	<10	256	<10	<1	118
57	A-96-170	255	<0.2	4.63	195	45	<5	2.50	<1	49	16	209	>10	<10	4.20	1534	3	0.02	15	2100	16	<5	<20	45	0.20	<10	301	<10	<1	169

El.#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
QC/DATA:																															
Repeat:																															
R/S 1	A-96-114	40	<0.2	2.49	10	90	<5	1.88	1	19	39	88	8.03	<10	1.88	1009	<1	0.02	7	2230	8	<5	<20	35	0.16	<10	85	<10	3	52	
R/S 36	A-96-149	30	<0.2	2.25	45	85	<5	1.09	<1	20	27	40	4.54	<10	1.83	692	2	0.03	3	1950	6	<5	<20	20	0.04	<10	75	<10	2	57	
Repeat:																															
1	A-96-114	30	<0.2	2.38	15	80	<5	1.77	1	18	35	84	5.88	<10	1.83	872	<1	0.02	7	2120	8	<5	<20	32	0.14	<10	78	<10	3	54	
10	A-96-123	35	<0.2	2.39	5	85	<5	4.14	2	32	28	201	6.85	<10	2.13	1091	<1	0.02	9	2020	6	<5	<20	80	0.17	<10	138	<10	2	45	
19	A-96-132	100	<0.2	1.81	75	105	<5	0.84	<1	77	32	97	4.42	<10	1.30	801	2	0.01	5	1930	28	<5	<20	18	0.08	<10	89	<10	3	82	
36	A-96-149	35	<0.2	2.16	35	80	<5	1.02	<1	20	17	39	4.37	<10	1.58	677	3	0.03	4	1800	6	<5	<20	18	0.04	<10	71	<10	1	54	
45	A-96-158	>1000	15.0	3.66	10000	65	<5	2.71	<1	876	27	1145	>10	<10	2.40	944	383	<0.01	8	1530	284	<5	<20	44	0.05	<10	192	<10	<1	877	
Standard:																															
GEO'96		150	1.2	1.80	65	170	<5	2.07	<1	21	72	83	4.02	<10	1.08	769	<1	0.02	20	780	22	<5	<20	60	0.15	<10	91	<10	4	75	
GEO'96		150	1.2	2.00	85	165	<5	1.96	<1	20	70	86	4.04	<10	1.07	762	<1	0.02	22	780	18	<5	<20	67	0.14	<10	89	<10	3	69	

dt/5079ar/5079r
XLS/96Teuton


ECO-TECH LABORATORIES LTD.
per Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AS 96-5079

TEUTON RESOURCES CORPORATION
 509-675 W. HASTINGS STREET
 VANCOUVER, B.C.
 V6C 1N2

22-Jul-96

ATTENTION: DINO CREMONESE

No. of samples received: 57
 PROJECT #: Clone
 SHIPMENT #: 7
 Samples submitted by: A. Raven

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	As (%)	Cu (%)	Co (%)
7	A-96-120	-	-	-	-	-	-	0.020
21	A-96-134	-	-	73.4	2.141	1.61	0.96	-
22	A-96-135	-	-	38.5	1.123	-	-	-
31	A-96-144	33.11	0.966	-	-	-	-	-
34	A-96-147	1.26	0.037	-	-	-	-	0.026
42	A-96-155	4.80	0.140	-	-	-	-	-
43	A-96-156	1.91	0.056	-	-	-	-	-
45	A-96-158	32.52	0.948	-	-	1.05	-	0.069
46	A-96-159	1.87	0.055	-	-	-	-	-
51	A-96-164	4.82	0.141	-	-	-	-	-
53	A-96-166	134.22	3.914	103.6	3.021	21.83	-	1.16
54	A-96-167	11.96	0.349	-	-	1.33	-	0.082

QC/DATA:

Standard:

CPb-1	-	-	632.0	18.431	-	-	-	-
CD-1	-	-	-	-	0.66	-	-	-
Sula	-	-	-	-	-	0.96	0.041	-

XLS/96Teuton#2

ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

22-Jul-98

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 98-5079

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 58
PROJECT #: Clove
SHIPMENT #: 7
Samples submitted by: A. Raven

Values in ppm unless otherwise reported

El. #	Tag #	As(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	A-98-114	30	<0.2	2.41	10	80	5	1.77	<1	18	35	95	5.69	<10	1.53	975	<1	0.02	7	2110	6	<5	<20	33	0.14	<10	79	<10	3	53
2	A-98-115	120	<0.2	2.34	15	75	<5	2.01	1	25	28	197	6.64	<10	1.84	994	<1	0.02	8	2160	6	<5	<20	31	0.14	<10	100	<10	2	44
3	A-98-116	10	0.6	2.45	35	90	<5	2.01	2	188	22	578	7.12	<10	1.96	1063	<1	0.01	9	2000	8	<5	<20	41	0.15	<10	113	<10	1	119
4	A-98-117	65	<0.2	1.89	10	130	<5	1.63	<1	20	23	73	4.41	<10	1.35	864	1	0.02	3	1870	4	<5	<20	77	0.09	<10	63	<10	2	41
5	A-98-118	50	<0.2	2.41	40	130	<5	2.33	3	130	29	456	7.86	<10	1.93	898	2	0.02	9	2140	24	<5	<20	43	0.15	<10	146	<10	2	71
6	A-98-119	235	<0.2	1.72	5	120	<5	1.21	1	13	31	76	3.27	<10	0.97	571	<1	0.03	3	1880	8	<5	<20	99	0.11	<10	51	<10	3	31
7	A-98-120	50	0.4	1.63	30	90	<5	1.84	<1	214	30	188	4.13	<10	1.27	757	2	0.01	4	1900	6	<5	<20	33	0.07	<10	69	<10	3	148
8	A-98-121	35	<0.2	1.95	<5	90	<5	1.01	2	78	24	303	4.49	<10	1.41	787	<1	0.02	3	1900	6	<5	<20	19	0.10	<10	70	<10	3	68
9	A-98-122	80	<0.2	3.84	15	85	<5	2.19	1	65	26	154	>10	<10	3.42	1561	3	0.02	18	2260	6	<5	<20	39	0.17	<10	198	<10	<1	98
10	A-98-123	50	<0.2	2.42	<5	70	<5	4.17	2	32	26	200	6.88	<10	2.11	1094	<1	0.02	10	1980	4	<5	<20	82	0.18	<10	140	<10	3	45
11	A-98-124	15	<0.2	1.75	15	120	<5	2.37	1	88	28	127	5.78	<10	1.26	736	1	0.03	8	1980	10	<5	<20	52	0.12	<10	111	<10	1	64
12	A-98-125	220	<0.2	1.82	30	90	<5	4.25	2	77	28	135	4.50	<10	1.27	914	<1	0.02	5	1950	10	<5	<20	62	0.12	<10	93	<10	2	61
13	A-98-126	75	<0.2	1.69	<5	80	<5	3.61	1	26	24	102	4.41	<10	1.16	645	2	0.03	5	2030	8	<5	<20	62	0.10	<10	81	<10	1	39
14	A-98-127	10	5.2	1.97	75	70	<5	0.58	8	34	31	592	4.81	<10	1.39	582	382	0.02	6	1990	8180	<5	<20	11	0.03	<10	80	<10	<1	73
15	A-98-128	30	<0.2	2.38	50	95	<5	0.61	<1	65	21	334	4.29	<10	1.65	771	4	0.02	4	2050	54	<5	<20	16	0.04	<10	60	<10	2	124
16	A-98-129	35	<0.2	2.32	30	90	<5	0.62	<1	59	26	293	4.06	<10	1.61	732	5	0.02	4	2080	30	<5	<20	11	0.04	<10	59	<10	2	118
17	A-98-130	310	<0.2	2.18	5	115	<5	1.07	1	22	18	80	5.34	<10	1.96	921	3	0.01	4	1960	16	<5	<20	22	0.07	<10	65	<10	2	235
18	A-98-131	150	<0.2	1.77	25	100	5	1.50	<1	83	29	37	5.26	<10	1.34	893	2	0.01	3	1900	10	<5	<20	31	0.06	<10	93	<10	<1	135
19	A-98-132	90	<0.2	1.79	70	100	<5	0.62	<1	74	28	98	4.27	<10	1.28	780	3	0.01	3	1830	22	<5	<20	17	0.06	<10	68	<10	3	78
20	A-98-133	45	<0.2	1.99	90	90	<5	1.07	<1	65	40	107	4.30	<10	1.41	765	2	0.01	7	1840	20	<5	<20	34	0.10	<10	84	<10	3	74
21	A-98-134	20	>30	1.16	10000	50	<5	2.31	<1	41	55	10000	9.47	<10	0.92	500	5	0.01	3	1040	14	185	<20	55	0.10	<10	82	<10	<1	52
22	A-98-135	505	>30	2.32	9170	50	<5	2.29	<1	45	55	6738	7.80	<10	1.55	629	3	0.01	3	1470	12	95	<20	102	0.17	<10	126	<10	<1	73
23	A-98-136	465	<0.2	2.55	95	105	<5	1.86	<1	17	55	198	5.22	<10	2.07	545	<1	0.01	5	2100	8	<5	<20	78	0.35	<10	219	<10	6	29
24	A-98-137	30	<0.2	2.46	35	30	<5	2.12	<1	33	58	185	5.23	<10	1.62	436	<1	0.03	2	2390	12	<5	<20	41	0.19	<10	155	<10	3	25
25	A-98-138	200	0.8	0.69	20	<5	<5	>10	<1	5	8	28	1.18	10	0.71	4072	<1	<0.01	2	270	<2	10	<20	432	0.03	<10	30	<10	11	11

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS AS 98-5079

ECO-TECH LABORATORIES LTD.

El #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	A-96-139	290	0.8	1.84	35	20	<5	>10	<1	12	18	31	3.04	10	1.65	4120	<1	<0.01	4	610	<2	15	<20	409	0.06	<10	48	<10	7	19
27	A-96-140	60	<0.2	2.97	65	35	5	1.03	<1	42	87	83	8.62	<10	3.01	1346	5	0.03	20	1870	26	<5	<20	18	0.13	<10	256	<10	<1	47
28	A-96-141	5	1.4	0.66	<5	20	<5	0.32	<1	8	172	128	1.45	<10	0.55	268	3	<0.01	4	370	2068	<5	<20	8	0.02	<10	26	<10	<1	23
29	A-96-142	256	0.8	2.48	220	90	<5	0.45	<1	28	35	416	4.99	<10	1.69	934	3	0.01	4	1910	18	<5	<20	9	0.02	<10	81	<10	2	168
30	A-96-143	40	4.8	0.77	45	55	<5	0.39	1	15	141	56	4.57	<10	0.25	102	61	<0.01	77	1850	60	15	<20	13	<0.01	<10	160	<10	2	233
31	A-96-144	>1000	15.2	1.24	370	135	<5	0.16	<1	140	42	845	>10	<10	0.86	649	35	<0.01	8	130	18	<5	<20	7	0.03	50	111	<10	<1	318
32	A-96-145	280	0.2	2.09	40	75	<5	0.88	<1	23	36	137	4.75	<10	1.54	763	5	0.02	3	1920	10	<5	<20	15	0.03	<10	73	<10	1	179
33	A-96-146	155	<0.2	2.08	105	70	<5	0.34	<1	110	42	134	4.68	<10	1.41	958	3	0.01	4	1270	10	<5	<20	6	0.04	<10	71	<10	4	163
34	A-96-147	>1000	0.6	4.21	715	80	<5	0.48	<1	270	51	410	>10	<10	3.28	1121	6	<0.01	11	1080	16	<5	<20	8	0.11	<10	181	<10	<1	231
35	A-96-148	80	<0.2	4.05	110	90	<5	0.54	2	43	19	184	8.78	<10	3.24	1033	7	0.01	14	2260	12	<5	<20	12	0.02	<10	170	<10	<1	133
36	A-96-149	25	<0.2	2.17	40	60	<5	1.01	<1	20	17	40	4.37	<10	1.60	680	2	0.03	3	1690	4	<5	<20	18	0.03	<10	71	<10	1	53
37	A-96-150	100	<0.2	1.74	40	65	<5	2.44	<1	36	25	36	4.00	<10	1.35	586	1	0.03	3	1920	6	<5	<20	41	0.06	<10	83	<10	4	48
38	A-96-151	430	<0.2	4.05	155	95	<5	1.95	<1	156	40	163	9.40	<10	3.53	1664	2	0.02	16	2180	<2	<5	<20	35	0.22	<10	190	<10	3	88
39	A-96-152	130	<0.2	4.02	135	85	<5	2.88	<1	123	21	373	>10	<10	3.40	1652	3	0.02	15	2210	4	<5	<20	80	0.24	<10	226	<10	<1	67
40	A-96-153	75	<0.2	3.06	70	70	<5	3.07	<1	30	20	183	7.14	<10	2.42	1131	2	0.03	8	2570	12	<5	<20	54	0.19	<10	178	<10	4	65
41	A-96-154	150	0.8	2.06	275	90	<5	1.07	<1	58	19	668	5.10	<10	1.21	816	5	0.01	4	1750	8	<5	<20	16	0.02	<10	60	<10	<1	163
42	A-96-155	>1000	6.0	3.70	2025	85	<5	0.37	<1	82	36	5196	>10	<10	2.38	1490	25	<0.01	3	1410	4	<5	<20	4	0.01	<10	125	<10	<1	436
43	A-96-156	>1000	2.2	2.53	290	100	<5	0.46	3	61	28	1257	6.85	<10	1.75	1664	11	<0.01	4	1670	4	<5	<20	5	0.02	<10	66	<10	1	321
44	A-96-157	685	0.6	2.83	270	105	<5	0.52	<1	88	22	426	6.62	<10	2.05	1049	7	<0.01	5	1810	6	<5	<20	7	0.06	<10	87	<10	<1	176
45	A-96-158	>1000	16.0	3.65	10000	55	<5	2.67	<1	661	24	1144	>10	<10	2.41	935	358	<0.01	6	1600	276	<5	<20	41	0.04	<10	190	<10	<1	857
46	A-96-159	>1000	2.4	3.58	245	45	<5	4.97	1	30	21	506	>10	<10	3.13	1264	61	0.02	9	2490	90	<5	<20	72	0.12	<10	264	<10	<1	220
47	A-96-160	165	<0.2	3.78	100	35	<5	5.13	<1	20	23	162	8.60	<10	3.31	1356	11	0.03	7	2710	22	<5	<20	78	0.17	<10	287	<10	2	85
48	A-96-161	105	0.2	2.78	745	70	<5	0.91	<1	29	13	133	5.94	<10	1.54	974	5	<0.01	6	2220	64	<5	<20	27	0.09	<10	76	<10	4	191
49	A-96-162	55	0.4	3.25	85	55	<5	3.57	1	31	14	147	6.52	<10	1.95	1495	3	<0.01	7	2910	98	<5	<20	80	0.11	<10	100	<10	6	194
50	A-96-163	40	<0.2	3.82	100	75	<5	0.87	<1	33	13	166	7.78	<10	2.26	1293	4	<0.01	7	3250	12	<5	<20	36	0.10	<10	106	<10	5	96
51	A-96-164	>1000	1.2	2.23	1535	50	<5	1.48	<1	171	21	224	6.94	<10	1.73	1046	12	0.02	8	1120	26	<5	<20	20	0.10	<10	83	<10	<1	54
52	A-96-165	95	<0.2	4.29	70	35	<5	4.13	<1	55	30	172	8.43	<10	4.11	1410	7	0.02	9	2720	12	<5	<20	72	0.19	<10	293	<10	3	143
53	A-96-166	>1000	>30	0.88	10000	60	<5	0.09	<1	10000	<1	2423	>10	<10	0.36	192	216	<0.01	<1	<10	3176	136	<20	11	<0.01	50	40	<10	<1	3363
54	A-96-167	>1000	7.6	5.18	10000	60	<5	0.53	<1	800	21	952	>10	<10	3.25	1089	66	<0.01	3	2070	242	<5	<20	9	0.06	<10	311	<10	<1	304
55	A-96-168	630	<0.2	4.72	1005	60	<5	3.62	<1	97	32	362	>10	<10	4.17	1218	14	0.02	16	2240	28	<5	<20	75	0.19	<10	323	<10	<1	82
56	A-96-169	445	1.0	4.11	395	55	<5	2.45	<1	60	30	933	>10	<10	3.11	1130	16	<0.01	24	2010	32	<5	<20	38	0.14	<10	256	<10	<1	118
57	A-96-170	255	<0.2	4.63	195	45	<5	2.50	<1	49	16	209	>10	<10	4.20	1534	3	0.02	16	2100	16	<5	<20	45	0.20	<10	301	<10	<1	169
58	-	-	7.2	5.21	10000	60	<5	0.54	<1	797	22	931	>10	<10	3.30	1100	63	<0.01	4	2140	246	<5	<20	8	0.06	<10	312	<10	<1	305

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS AS 96-6079

ECO-TECH LABORATORIES LTD.

El #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
------	-------	---------	----	------	----	----	----	------	----	----	----	----	------	----	------	----	----	------	----	---	----	----	----	----	------	---	---	---	---	----

QC/DATA:

Repeat:

R/S 1 A-98-114	40	<0.2	2.49	10	90	<5	1.88	1	19	39	88	8.03	<10	1.88	1009	<1	0.02	7	2230	8	<5	<20	35	0.18	<10	85	<10	3	52
R/S 36 A-98-149	30	<0.2	2.25	45	85	<5	1.09	<1	20	27	40	4.54	<10	1.63	892	2	0.03	3	1950	6	<5	<20	20	0.04	<10	75	<10	2	57

Repeat:

1 A-98-114	30	<0.2	2.38	15	80	<5	1.77	1	18	35	84	5.88	<10	1.83	972	<1	0.02	7	2120	8	<5	<20	32	0.14	<10	78	<10	3	54
10 A-98-123	35	<0.2	2.39	5	85	<5	4.14	2	32	26	201	6.85	<10	2.13	1091	<1	0.02	9	2020	8	<5	<20	60	0.17	<10	138	<10	2	45
19 A-98-132	100	<0.2	1.81	75	105	<5	0.84	<1	77	32	97	4.42	<10	1.30	801	2	0.01	5	1930	26	<5	<20	18	0.06	<10	89	<10	3	82
38 A-98-149	35	<0.2	2.18	35	80	<5	1.02	<1	20	17	39	4.37	<10	1.58	877	3	0.03	4	1900	6	<5	<20	18	0.04	<10	71	<10	1	54
45 A-98-158	>1000	15.0	3.88	10000	85	<5	2.71	<1	878	27	1145	>10	<10	2.40	944	363	<0.01	6	1530	284	<5	<20	44	0.05	<10	192	<10	<1	877

Standard:

GEO'98	150	1.2	1.80	85	170	<5	2.07	<1	21	72	83	4.02	<10	1.08	789	<1	0.02	20	780	22	<5	<20	60	0.15	<10	91	<10	4	75
GEO'98	150	1.2	2.00	85	165	<5	1.96	<1	20	70	88	4.04	<10	1.07	762	<1	0.02	22	780	18	<5	<20	67	0.14	<10	89	<10	3	69

dl/5079ar/5079r
XLS/98Teuton

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

22-Jul-98

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5087

TEUTON RESOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 20
PROJECT #: Clone
SHIPMENT #: 8
P.O.#: None Given
Samples submitted by: M. Moorman

Values in ppm unless otherwise reported

El #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	MM98-001	10	0.4	2.18	15	45	<5	0.72	<1	51	18	188	9.70	<10	1.15	379	9	<0.01	15	3820	58	<5	<20	18	<0.01	<10	75	<10	<1	44
2	MM98-002	15	2.2	1.35	70	35	10	1.50	<1	23	69	74	>10	<10	1.08	272	22	<0.01	81	1100	46	<5	<20	28	<0.01	<10	22	<10	<1	79
3	MM98-003	70	4.1	5.08	5	175	<5	0.48	<1	101	73	199	8.33	<10	3.20	1675	9.8	<0.01	17	2161	446	<5	<20	10	0.01	<10	209	<10	<1	1320
4	MM98-004	35	1.8	4.09	90	120	<5	0.55	1	61	45	272	>10	<10	2.18	1451	13	<0.01	15	1610	296	<5	<20	22	<0.01	<10	185	<10	<1	1161
5	D-98-69	5	<0.2	2.58	5	40	<5	3.00	<1	44	71	325	5.61	<10	0.88	407	3	0.10	34	2470	52	<5	<20	99	0.17	<10	128	<10	<1	103
6	D-98-70	5	<0.2	1.73	25	40	<5	2.12	<1	37	58	189	4.60	<10	0.76	342	<1	0.03	36	2680	48	<5	<20	38	0.15	<10	99	<10	3	73
7	D-98-71	20	<0.2	2.87	30	45	<5	2.57	<1	48	145	206	5.49	<10	1.05	461	26	0.18	38	2550	46	<5	<20	192	0.24	<10	134	<10	1	105
8	D-98-72	5	<0.2	2.36	10	40	<5	2.14	<1	39	122	129	5.63	<10	1.45	504	<1	0.07	40	2830	40	<5	<20	76	0.29	<10	171	<10	2	82
9	D-98-73	5	0.6	2.55	10	40	<5	1.53	1	55	62	202	7.79	<10	2.23	843	2	0.04	49	2620	70	<5	<20	38	0.15	<10	99	<10	<1	133
10	D-98-74	10	1.2	1.80	165	30	<5	2.95	<1	75	56	652	7.21	<10	0.27	319	6	0.03	178	2280	34	<5	<20	40	0.07	<10	36	<10	<1	82
11	D-98-75	5	<0.2	2.35	35	40	<5	2.16	<1	50	140	204	5.67	<10	1.22	466	3	0.06	49	2690	40	<5	<20	97	0.20	<10	132	<10	1	79
12	D-98-76	5	<0.2	2.35	20	45	<5	2.03	<1	39	125	384	5.30	<10	1.21	354	<1	0.09	37	1980	32	<5	<20	130	0.20	<10	121	<10	<1	41
13	D-98-77	5	<0.2	1.96	<5	70	<5	2.82	2	115	127	699	>10	<10	0.70	378	10	0.02	110	4150	22	<5	<20	64	0.11	<10	108	<10	<1	38
14	D-98-78	5	<0.2	1.89	45	60	<5	2.93	<1	65	116	531	9.04	<10	0.45	310	6	0.02	57	3710	36	<5	<20	40	0.13	<10	117	<10	<1	35
15	D-98-79	5	<0.2	1.45	25	35	<5	2.37	<1	62	60	516	7.66	<10	0.37	231	4	0.08	46	3220	22	<5	<20	55	0.12	<10	87	20	<1	26
16	D-98-80	5	<0.2	3.38	<5	50	<5	2.14	<1	41	68	131	7.30	<10	2.97	1111	<1	0.03	20	2000	32	<5	<20	27	0.18	<10	218	<10	1	60
17	D-98-81	5	<0.2	2.97	<5	50	<5	1.66	1	46	40	149	9.24	<10	2.54	1314	<1	0.04	18	3070	30	<5	<20	42	0.32	<10	296	<10	5	100
18	D-98-82	5	1.4	3.32	30	45	<5	1.03	<1	52	38	164	>10	<10	3.70	873	6	0.05	18	2710	50	<5	<20	20	0.13	<10	273	<10	<1	107
19	D-98-83	5	<0.2	3.63	15	35	<5	1.37	<1	43	18	175	9.48	<10	3.28	1766	5	0.03	14	2450	46	<5	<20	19	0.20	<10	321	<10	1	119
20	D-98-84	5	7.0	0.64	340	45	20	0.21	<1	31	54	82	>10	<10	0.35	53	44	<0.01	104	300	102	<5	<20	3	<0.01	30	10	<10	<1	86

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS-5087

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
QC/DATA:																															
Repeat:																															
RS / 1	MM96-001	10	0.4	2.15	10	45	<5	0.71	<1	53	15	168	9.94	<10	1.14	398	9	<0.01	14	3810	56	<5	<20	18	<0.01	<10	74	<10	<1	44	
Repeat:																															
1	MM96-001	5	0.4	2.27	15	50	<5	0.74	<1	52	19	168	9.95	<10	1.17	388	9	<0.01	15	3750	62	<5	<20	18	<0.01	<10	78	<10	<1	45	
10	D-96-74	10	0.8	1.87	170	25	<5	3.06	<1	78	56	849	7.10	<10	0.26	320	9	0.03	174	2210	32	<5	<20	37	0.07	<10	36	<10	<1	77	
Standard:																															
GEO'95		-	1.8	1.94	70	170	<5	2.20	<1	24	75	82	4.10	<10	1.05	710	<1	0.02	24	720	24	<5	<20	81	0.14	<10	88	<10	5	74	

dl/5085r
XLS/96Teuton#2

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

G E O C H E M I C A L A N A L Y S I S C E R T I F I C A T E

TEUTON RESOURCES CORP.

Project: Clone
Sample Type: Rocks

Multi-element ICP Analysis - .500 gram sample is digested with 3 ml of aqua regia, diluted to 10 ml with water. This leach is partial for Mn, Fe, Ca, P, La, Cr, Mg, Ba, Ti, B, W and limited for Na, K and Al. Detection Limit for Au is 3 ppm.
*Au Analysis- 10 gram sample is digested with aqua regia, MIBK extracted, graphite furnace AA finished to 1 ppb detection.

Analyst RSam
Report No. 9621793
Date: August 12, 1996

ELEMENT SAMPLE	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
D96 085	1	226	3	43	.3	27	44	398	5.00	17	5	ND	2	32	.2	2	2	122	1.56	.095	3	29	1.39	38	.11	7	2.27	.05	.13	2	27
D96 086	3	6	3	19	.3	1	2	81	3.80	9	5	ND	13	12	.2	2	2	9	.06	.030	8	30	.15	150	.04	3	.47	.05	.16	2	13
D96 087	1	51	6	39	.4	9	23	2030	5.70	18	5	ND	2	129	.2	2	2	73	6.76	.101	5	10	1.86	27	.01	4	1.12	.02	.20	2	11
D96 088	1	1413	58	3537	8.0	220	67	3421	22.85	672	5	ND	3	348	44.5	2	2	52	10.69	.009	4	28	1.49	12	.01	3	1.18	.01	.03	2	42
D96 089	1	460	150	476	11.1	57	118	828	26.57	2107	5	ND	3	3	.6	11	6	142	.07	.016	2	39	2.41	1	.01	7	2.09	.01	.02	2	105
D96 090	1	2012	179	2140	11.1	79	289	1812	32.10	719	5	ND	3	30	23.2	2	2	53	2.00	.011	3	16	1.72	9	.01	3	1.56	.01	.04	2	24
D96 091	1	2520	92	355	14.6	99	94	2333	20.89	627	5	ND	3	143	4.9	16	8	140	10.22	.016	3	39	2.59	15	.01	3	1.93	.01	.40	2	37
D96 092	1	1965	64	136	23.2	511664	567	34.42	58245	5	ND	3	9	.2	185	112	56	.49	.011	2	33	.71	7	.01	6	.77	.01	.11	2	120	
D96 093	1	999	3	159	.9	37	146	1485	33.85	2721	5	ND	4	88	4.3	2	9	75	6.24	.001	6	5	1.36	1	.01	3	1.25	.01	.01	2	37
D96 094	1	398	79	66	7.3	37	45	3873	13.69	600	5	ND	2	291	1.2	52	2	33	11.79	.014	4	33	1.75	28	.01	3	.70	.01	.04	2	33
D96 095	1	2203	18	56	12.5	24	50	1298	28.37	938	5	ND	3	86	1.4	2	2	105	4.82	.037	4	53	1.27	10	.03	4	1.26	.01	.22	13	24
D96 096	1	736	206	130	18.8	19	212	3539	28.25	20640	5	ND	3	154	1.3	78	28	106	4.52	.019	2	42	2.13	16	.01	6	1.61	.01	.30	2	140
D96 097	3	10	6	38	.3	11	16	1007	2.59	20	5	ND	2	32	.2	2	2	51	2.94	.054	5	77	.93	54	.01	5	1.30	.01	.17	2	6
D96 098	3	30	12	78	.3	12	13	1759	5.14	36	5	ND	2	235	.8	2	2	22	10.28	.014	5	88	2.45	11	.01	3	.49	.01	.04	2	8
D96 099	1	152	2350	3641	10.6	1	16	8188	15.93	1734	5	ND	2	374	38.7	33	2	19	13.07	.008	3	21	2.71	1	.01	3	.50	.01	.06	2	275
D96 100	1	494	823	194	59.3	4	86	7332	14.64	4143	5	ND	2	268	1.9	271	2	19	12.21	.006	3	27	3.64	13	.01	3	.32	.01	.05	2	340
D96 101	4	9	43	197	1.7	3	13	3125	2.94	392	5	ND	2	522	2.3	21	8	24	15.12	.009	3	96	1.39	1	.01	3	.33	.01	.02	2	31
D96 102	1	451	633	49924	48.1	391021	4222	24.75	20875	5	ND	2	62	640.5	401	189	11	3.65	.001	2	37	1.51	1	.01	4	.16	.01	.04	2	620	
D96 103	1	192	665	35720	27.0	20	29	5504	16.16	1806	5	ND	2	153	510.6	210	4	31	6.66	.042	3	38	2.12	29	.01	3	.43	.01	.12	2	280
D96 104	1	459	29	154	2.4	8	36	1645	46.17	330	5	ND	5	37	.2	2	2	6	1.48	.001	2	18	.22	5	.01	3	.13	.01	.02	2	95
D96 105	1	272	188	121	5.1	2	67	4715	24.27	3915	5	ND	2	155	.4	31	3	21	6.17	.003	2	23	2.10	4	.01	3	.51	.01	.05	2	190
D96 106	1	109	37	56	1.8	8	20	7137	16.76	440	5	ND	2	280	1.7	15	2	115	9.85	.077	7	40	2.57	40	.05	3	1.61	.01	.57	2	38
D96 107	1	150	45	94	2.5	14	12	1153	14.46	653	5	ND	2	146	.2	27	2	170	1.89	.168	7	49	1.54	31	.01	5	1.62	.01	.52	2	23
D96 108	1	173	6	78	.3	18	31	512	6.12	16	5	ND	2	35	.2	2	2	186	1.77	.165	7	52	1.69	51	.27	3	2.61	.04	.81	2	12
A96 171	1	135	16	125	.3	22	31	706	5.71	21	5	ND	2	21	.3	2	2	167	1.80	.112	2	18	1.65	29	.13	9	2.86	.06	.10	2	90
A96 172	1	161	263	349	22.1	10	8	841	10.06	75	5	ND	2	19	.4	33	2	155	.21	.112	4	16	2.15	35	.01	3	3.32	.01	.20	2	12
A96 173	1	106	3	67	.4	9	9	2458	7.77	2	5	ND	2	85	.2	2	2	334	2.68	.146	7	54	3.86	15	.03	3	4.21	.02	.04	2	195
A96 174	1	20	10	32	.4	2	14	2228	4.50	12	5	ND	2	233	.2	.2	2	43	6.62	.107	11	8	1.99	89	.01	3	1.16	.01	.34	2	12
A96 175	1	15	5	37	.3	1	8	3949	7.32	29	5	ND	2	57	.2	2	2	62	4.94	.090	10	10	1.02	98	.01	3	2.16	.01	.22	2	15
A96 176	1	79	10	72	.3	11	19	1939	5.89	173	5	ND	2	347	.9	13	2	125	10.55	.090	6	33	3.26	342	.04	4	1.53	.01	.56	2	33

ELEMENT SAMPLE	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au ppb
A96 177	1	15	3	39	.3	15	61	694	21.13	642	5	ND	3	8	.2	2	2	123	.14	.058	2	64	2.80	13	.01	7	3.52	.01	.10	2	50
A96 178	1	16	3	33	.3	5	14	4095	5.87	115	5	ND	2	313	1.3	2	2	83	20.48	.019	5	13	3.48	46	.01	3	2.40	.01	.02	2	620
A96 179	1	150	3	72	.3	22	23	776	6.38	2	5	ND	2	22	.2	2	2	271	.77	.127	2	44	2.16	37	.17	3	2.84	.07	.09	2	15
A96 180	2	3	3	11	.3	4	2	504	.95	13	5	ND	2	325	.3	3	2	40	2.44	.009	1	33	.16	7	.01	310	1.13	.01	.02	2	16
A96 181	2	109	13	65	.6	25	24	552	4.70	22	5	ND	2	132	.2	5	2	138	1.55	.133	3	103	2.05	130	.17	3	2.72	.26	.50	2	31
A96 182	1	4	3	12	.3	8	2	475	.48	24	5	ND	2	353	.2	2	2	15	8.45	.016	1	36	.31	1	.02	506	.36	.01	.01	2	160
A96 183	6	10	3	8	.3	4	1	76	.43	5	5	ND	2	11	.2	2	2	3	.10	.023	1	145	.02	20	.01	3	.11	.03	.03	2	6
A96 184	20	274	56	132	2.6	8	192	913	5.56	1611	5	7	2	7	.2	4	3	70	.40	.110	7	14	1.66	64	.04	3	2.31	.01	.27	2	7150
A96 185	12	150	31	138	1.2	10	190	999	5.69	8262	5	4	2	24	.4	8	2	122	1.16	.111	8	23	2.08	66	.02	3	2.62	.01	.18	2	3520
A96 186	4	145	7	116	1.0	18	512	1014	5.80	7619	5	3	2	12	.2	3	2	163	.49	.135	8	27	2.06	84	.05	3	2.84	.02	.16	2	2680
A96 187	11	164	25	83	2.2	12	56	774	6.42	2823	5	ND	2	8	.2	4	2	130	.41	.123	7	24	1.63	45	.07	3	2.42	.01	.16	2	325
A96 188	9	266	21	136	2.1	11	101	1152	5.14	1600	5	ND	2	26	.3	2	2	85	1.57	.127	7	18	1.75	52	.07	3	2.62	.01	.32	2	1220
A96 189	11	479	24	87	1.9	101277	760	8.84	23021	10	3	2	22	.2	12	7	130	.99	.094	4	18	2.21	41	.05	3	2.66	.01	.13	2	4030	
A96 190	13	450	22	96	2.0	13	246	795	8.56	3196	5	ND	2	21	.2	3	12	164	1.07	.101	5	22	2.28	43	.08	3	2.71	.01	.12	2	1260
A96 191	78	291	129	488	26.7	71009	1407	7.62	12343	9	78	2	25	4.4	10	5	135	1.43	.113	6	24	1.91	58	.02	3	2.79	.01	.19	2	78020	
A96 192	27	370	118	671	6.0	8	682	1489	8.30	7629	5	8	2	25	9.9	6	3	145	1.39	.114	8	26	2.51	53	.04	3	3.28	.01	.22	2	9070
A96 193	4	165	71	53	9.0	1	66	468	20.08	338	5	80	3	17	.2	29	136	284	.38	.088	6	23	.14	147	.09	3	.64	.01	.36	13	79800
A96 194	1	103	18	430	.3	5	91	1192	3.36	33	5	ND	2	39	.6	4	2	69	1.14	.156	7	11	.80	151	.09	3	1.33	.02	.35	2	740
A96 195	1	62	26	140	.5	3	21	692	5.33	51	5	ND	2	40	.2	10	19	82	1.70	.135	7	20	.41	145	.10	3	.85	.01	.39	2	1530
A96 196	1	47	44	228	.3	1	50	1693	8.41	74	5	ND	2	34	.2	8	10	83	1.68	.125	6	8	1.08	140	.08	8	1.73	.01	.43	3	440
A96 197	1	24	28	48	.3	1	2	1044	3.28	37	5	ND	2	42	.5	8	2	46	1.95	.141	5	5	.21	132	.09	4	.93	.01	.49	2	175
A96 198	6	49	23	157	.3	10	19	2803	6.49	35	5	ND	2	184	1.5	2	2	200	12.64	.126	10	21	4.16	17	.04	3	3.96	.01	.09	2	90
A96 199	4	199	9	89	.7	5	44	1565	7.15	154	5	ND	2	83	.3	2	4	210	5.30	.174	8	9	3.64	34	.08	3	3.79	.02	.10	2	65
A96 200	7	150	3	95	.3	12	21	1563	7.70	47	5	ND	2	95	.5	2	4	319	5.46	.179	9	28	4.24	23	.19	3	4.18	.02	.08	2	47
A96 201	3	134	3	104	.3	23	40	1807	8.77	139	5	ND	2	142	1.1	2	2	323	7.96	.120	6	69	5.94	21	.21	3	5.21	.01	.22	2	35
A96 202	61	861	51	81	3.0	90	196	1620	17.05	372	5	ND	2	45	4.0	2	6	304	2.30	.111	5	63	5.30	18	.20	3	4.72	.01	.23	2	480
A96 203	21	194	3	107	.3	13	33	1673	8.22	83	5	ND	2	59	.4	2	2	296	3.08	.165	8	32	4.89	39	.16	3	4.64	.01	.15	2	180
A96 204	1	161	3	93	.3	6	26	1185	7.37	139	5	ND	2	27	.2	2	2	247	1.15	.197	11	7	3.73	59	.10	3	4.05	.02	.16	2	70
A96 205	4	298	4	85	.8	2	35	828	7.60	183	5	ND	2	16	.2	2	7	209	.73	.236	8	12	2.95	34	.10	3	3.33	.01	.32	2	120
A96 206	50	19473	3	109	33.9	100	71	1604	10.71	89	5	4	2	19	.4	2	2	163	1.62	.068	8	67	2.54	49	.02	3	3.35	.01	.18	2	5250
A96 207	111	643	40	15	2.1	65	135	429	15.97	525	5	ND	2	5	.2	3	28	86	.06	.053	2	45	.36	21	.01	4	.85	.01	.14	2	505
A96 208	4	97	67	15	2.5	1	17	182	8.19	18	5	ND	2	5	.2	9	27	22	.03	.045	5	10	.28	13	.01	3	.81	.01	.31	2	210
A96 209	2	1655	7	135	1.1	21054	1102	4.35	5424	5	ND	3	20	4.4	4	2	113	1.03	.100	14	13	2.03	71	.02	3	1.97	.01	.15	2	2030	
A96 210	7	2078	40	150	2.3	81983	775	11.13	19773	5	3	3	9	6.7	20	2	143	.36	.069	7	15	2.04	15	.01	3	2.42	.01	.10	2	3360	
A96 211	2	483	10	132	.6	2	96	879	4.93	464	5	ND	3	38	7.0	2	2	134	2.10	.098	13	13	1.94	42	.05	3	2.11	.02	.13	2	480

ELEMENT SAMPLE	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au ppb
A96 212	17	394	5	184	.4	12	38	1917	9.10	103	5	ND	2	48	2.1	2	2	289	2.71	.149	8	33	4.30	53	.21	3	4.43	.02	.12	2	47
A96 213	10	375	10	131	.3	9	80	1512	6.74	156	5	ND	2	29	.7	2	2	197	1.48	.126	10	24	2.94	110	.16	3	3.21	.01	.13	3	320
A96 214	2	112	13	103	.3	4	15	940	4.38	53	5	ND	2	26	.2	2	4	121	1.13	.115	14	16	1.95	51	.05	3	2.22	.03	.13	2	26
A96 215	7	116	10	116	.3	3	14	674	3.86	41	5	ND	2	42	.2	2	2	92	1.46	.128	9	10	1.71	36	.01	3	1.95	.03	.15	2	150
A96 216	9	367	10	141	.8	1	121	882	4.95	263	5	ND	2	24	.2	2	4	106	.95	.109	9	8	2.08	43	.01	3	2.31	.01	.14	2	145
A96 217	3	696	8	111	1.0	5	27	852	4.55	111	5	ND	3	34	.3	2	2	95	1.31	.091	14	13	1.81	42	.01	3	2.11	.01	.13	2	105
A96 218	12	2399	11	127	4.9	4	169	750	4.75	1158	5	ND	2	26	2.8	4	2	84	.89	.110	11	13	1.72	44	.01	3	2.00	.02	.16	2	60
A96 219	3	62	3	65	.3	3	14	737	3.65	46	5	ND	2	90	.2	2	2	80	3.19	.117	7	16	1.81	26	.04	3	2.11	.03	.18	2	135
A96 220	1	144	3	111	.3	10	481	1214	5.39	279	5	ND	2	17	.2	2	2	129	.77	.149	11	15	2.52	67	.02	3	2.89	.01	.27	2	240
A96 221	4	252	5	95	.4	17	52	1854	7.73	106	5	ND	2	23	.2	2	2	245	.82	.163	9	28	3.51	67	.05	3	3.50	.03	.11	2	75
A96 222	7	421	13	76	.7	14	49	900	7.97	77	5	ND	2	23	.2	2	2	168	1.09	.176	7	20	1.79	41	.04	3	2.31	.03	.16	2	105
A96 223	5	268	7	71	.6	10	30	843	6.06	49	5	ND	2	21	.2	2	2	157	1.03	.187	8	19	1.63	45	.02	3	2.18	.04	.16	2	110
A96 224	4	56	22	150	.7	8	8	1478	4.13	123	5	3	2	79	1.3	2	3	84	4.66	.093	6	17	2.27	41	.07	3	2.60	.02	.21	2	3520
A96 225	15	873	47	142	1.5	6	28	1216	4.20	31	5	ND	2	54	.8	4	2	53	3.32	.092	9	7	1.48	133	.07	3	2.07	.01	.35	2	820
A96 226	1	119	3	154	.6	14	26	1023	6.81	54	5	ND	2	35	.2	7	2	77	1.54	.126	8	16	1.44	68	.07	3	2.20	.01	.40	2	270
A96 227	2	284	10	64	.3	3	24	505	4.93	45	5	ND	2	45	.2	5	2	56	1.46	.127	8	7	.47	134	.06	3	1.04	.01	.43	3	205
A96 228	6	1834	34	74	3.5	2	94	522	4.36	188	5	ND	2	27	.2	5	3	59	.90	.118	6	13	.72	304	.03	10	1.41	.01	.50	2	760
A96 229	7	692	29	80	.7	4	6	500	9.55	90	5	ND	2	20	.2	9	4	74	.67	.129	9	7	.44	290	.06	6	1.26	.01	.53	5	1040
A96 230	1	269	5	115	.3	5	8	706	4.00	20	5	ND	2	23	.2	2	2	46	.91	.144	7	6	.90	278	.05	3	1.81	.01	.59	2	60
A96 231	1	1050	8	72	.9	2	8	718	3.24	33	5	ND	2	34	.7	4	2	33	1.48	.135	7	4	.70	282	.04	3	1.52	.01	.60	2	110
A96 232	1	174	10	168	.3	5	10	880	4.48	29	5	ND	2	39	.5	6	2	48	1.58	.131	7	15	.82	164	.05	3	1.53	.01	.48	2	890
A96 233	1	119	11	114	.3	2	10	1190	3.80	35	5	ND	2	14	.7	2	2	44	.60	.142	10	4	1.05	160	.04	5	1.95	.01	.55	2	95
A96 234	1	1148	20	89	1.0	4	8	1332	5.34	160	5	ND	2	15	1.8	12	2	58	.57	.127	10	5	.26	141	.06	4	.85	.01	.41	2	130
A96 235	1	170	33	216	.3	12	29	926	6.20	120	5	ND	2	13	.3	4	2	97	.42	.134	8	18	1.38	199	.11	6	1.95	.01	.42	2	750
A96 236	1	243	10	80	.3	3	22	888	2.79	14	5	ND	2	79	.5	3	2	29	3.91	.130	7	3	.92	254	.03	5	1.83	.01	.58	2	145
A96 237	1	152	23	94	.3	5	13	865	2.92	31	5	ND	2	34	.4	2	2	29	1.50	.138	8	3	.76	287	.03	5	1.72	.01	.57	2	65
A96 238	1	347	19	132	.4	3	10	1038	3.28	51	5	ND	2	26	3.8	3	2	32	1.22	.135	10	3	.53	206	.03	3	1.43	.01	.52	2	340
A96 239	4	110	22	98	.3	3	4	701	5.43	171	5	ND	2	19	.2	12	2	58	.69	.118	9	5	.33	140	.04	3	1.07	.01	.44	2	380
A96 240	2	2418	5	159	3.6	3	7	917	3.93	105	5	ND	2	17	3.2	22	2	47	.72	.143	7	5	.70	160	.04	5	1.52	.01	.55	2	115
A96 241	1	186	4	77	.3	4	9	903	3.15	40	5	ND	2	55	.5	4	2	39	2.54	.132	8	4	.82	180	.06	6	1.45	.01	.49	2	255
A96 242	1	55	16	88	.3	3	7	817	4.30	31	5	ND	2	38	.2	5	2	51	1.14	.133	10	5	.40	893	.07	3	1.04	.01	.47	2	390

For Cu, Zn greater than 10,000 ppm, assay digestion is required for correct data.

For Ag greater than 35 ppm, assay digestion is required for correct data.

PIONEER LABORATORIES INC. 5-730 EATON WAY NEW WESTMINSTER, BC CANADA V3M 6J9 TELEPHONE (604) 522-3830

GEOCHEMICAL ANALYSIS CERTIFICATE

TEUTON RESOURCES CORP.

Project: Clone

Report No. 9621819

Sample Type: Rocks

Date: August 17, 1996

Multi-element ICP Analysis - .500 gram sample is digested with 3 ml of aqua regia, diluted to 10 ml with water. This leach is partial for Mn, Fe, Ca, P, La, Cr, Mg, Ba, Ti, B, W and limited for Na, K and Al. Detection Limit for Au is 3 ppm.

*Au Analysis- 10 gram sample is digested with aqua regia, MIBK extracted, graphite furnace AA finished to 1 ppb detection.

ELEMEN	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Au*
SAMPLE	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppb
D96-109	688	28448	5	524	6.5	167	166	3039	7.77	40	5	ND	5	91	9.6	5	19	305	7.3	1.6	72	62	3.3	23	0	3	3.4	0	0.1	2	280
D96-110	11181	19283	21	210	50.2	159	55	736	15.13	62	5	ND	5	14	0.7	2	20	333	1.2	0.5	19	67	2.4	9	0.1	3	2.5	0	0	2	2080
D96-111	9822	17866	3	120	44.3	119	97	537	14.98	43	5	3	5	15	0.2	3	18	332	1.2	0.6	24	115	1.9	6	0.1	3	2.3	0	0	2	3980
D96-112	34	373	9	39	12.6	9	92	1295	5.55	35	5	17	2	95	0.2	2	2	22	2.6	0	3	101	0.5	43	0	3	0.8	0	0.2	2	18850
D96-113	14	551	9	85	10.6	8	82	2273	7.27	32	5	ND	2	208	0.4	4	2	38	5.4	0	3	59	1.3	53	0	3	1.7	0	0.1	2	1650
D96-114	44	147	108	188	0.9	19	52	1286	7.26	320	5	ND	2	14	0.9	2	2	127	0.4	0.2	5	37	3.1	99	0	3	3.5	0	0.2	2	110
D96-115	52	264	222	116	1.5	18	33	744	8.01	641	5	ND	2	9	0.2	6	2	99	0.3	0.2	3	35	2.2	33	0	3	2.4	0	0.1	2	115
D96-116	93	152	54	132	0.8	25	34	1077	6.87	393	5	ND	2	12	0.2	2	2	142	0.4	0.2	5	33	2.9	109	0	3	3.1	0	0.1	2	59
D96-117	2	40	8	98	0.3	14	19	960	7.89	24	5	ND	2	14	0.2	2	2	130	0.5	0.2	10	27	2.2	63	0.1	3	2.5	0	0.2	2	1120
D96-118	1	36	6	79	0.3	18	20	1048	10.28	6	5	ND	2	12	0.2	2	2	198	0.4	0.2	8	18	3.5	67	0.1	3	3.5	0	0.3	3	10
D96-119	1	59	8	78	0.3	16	24	1611	4.24	57	5	ND	2	83	0.2	2	2	95	3.9	0.1	4	28	1.8	88	0.1	3	2	0	0.2	2	12
D96-120	9	215	32	94	0.7	17	25	1269	6.99	215	5	ND	2	20	0.7	2	2	107	0.8	0.2	4	22	2.3	120	0	3	2.9	0	0.2	51	47
D96-121	548	45	2724	585	5.1	16	27	1153	8.02	641	5	ND	2	11	9.9	7	2	88	0.5	0.1	4	23	2.2	51	0	3	2.7	0	0.2	2	160
D96-122	6	57	36	93	0.3	4	27	1046	4.14	97	5	ND	2	31	0.4	2	2	48	1.6	0.1	12	5	1.1	129	0	3	1.7	0	0.4	2	605
D96-123	2	61	6	64	0.3	4	20	705	4.11	49	5	ND	3	15	0.2	2	2	42	0.7	0.1	10	10	1.5	62	0.1	3	2	0	0.3	2	27
D96-124	144	70043	27	40	133.1	74	155	350	19.95	358	5	3	2	2	0.2	24	2	59	0.1	0	1	84	0.6	4	0	3	0.9	0	0	2	2020
D96-125	8	1640	6	26	1.7	50	29	924	10.76	64	5	ND	2	49	0.2	2	2	69	0.8	0	2	163	1	34	0	3	2.5	0.1	0.1	150	31
D96-126	36	4422	7	47	7.1	13	102	623	9.34	73	5	ND	2	33	0.2	5	6	90	0.8	0.1	7	46	0.9	11	0.1	3	1.8	0.1	0.1	###	380
D96-127	12	391	3	39	0.3	5	19	912	4.99	14	5	ND	2	18	0.2	3	2	131	0.6	0.1	6	124	1.4	14	0.1	3	2.3	0	0.1	980	51
D96-128	6	4909	6	65	1.6	6	96	1229	13.38	10	5	ND	2	78	0.2	2	6	43	1.7	0.1	3	42	0.7	15	0.1	3	3.6	0.1	0.1	343	42
D96-129	55	7749	4	32	1.7	4	50	1434	17.77	26	5	ND	2	24	0.2	3	2	175	1.2	0	3	41	0.6	6	0.1	3	1.6	0	0	720	36
D96-130	16	1321	3	16	0.7	5	26	977	15.8	26	5	ND	2	39	0.2	4	2	45	0.7	0.1	5	51	0.9	14	0.1	3	2.1	0.1	0.1	729	47
D96-131	5	3426	3	39	1.4	12	84	749	15.22	18	5	ND	2	34	0.2	2	2	57	1.1	0.1	4	34	1	11	0.1	3	2.3	0.1	0.1	127	80
D96-132	15	3970	18	67	16.5	5	104	1667	21.79	270	5	ND	2	17	0.2	5	2	78	0.4	0.1	4	33	1	14	0.1	4	3.2	0.1	0.1	157	85
D96-133	12	2318	15	35	6.1	6	114	667	20	48	5	ND	2	12	0.2	2	2	57	0.2	0	2	44	0.6	6	0.1	3	1.5	0	0	476	195
A96-243	4	515	13	139	0.3	3	13	878	5.12	33	5	ND	2	55	0.3	4	2	40	2.2	0.1	6	15	0.5	321	0	4	1.2	0	0.5	2	90
A96-244	1	1275	23	192	3.6	3	13	1665	5.22	28	5	ND	2	15	2.3	2	2	48	0.6	0.1	8	6	1.2	187	0	4	1.8	0	0.4	2	145
A96-245	2	145	23	126	0.3	3	24	1271	5.22	34	5	ND	2	50	0.7	9	2	48	2	0.1	7	8	0.6	152	0	3	1.2	0	0.4	2	180

MM96-01 1	8	4	54	0.3	4	79	933	11.41	2	5	ND	2	6	0.2	2	2	50	0.4	0.1	1	11	2.6	16	0.1	3	3	0	0.3	5	28
MM96-01 2	8	3	22	0.3	4	15	656	5.69	2	5	ND	2	9	0.2	2	2	32	0.6	0.1	2	12	1.3	19	0.1	3	1.9	0	0.4	2	18
MM96-01 2	8	3	160	0.3	7	30	3096	18.07	40	5	ND	2	5	0.2	2	2	219	0.4	0.1	1	5	4.9	65	0.1	3	7.5	0	0.2	2	25
MM96-01 12	38	34	26	1.7	4	60	436	9.43	24	5	ND	2	5	0.2	4	10	32	0.1	0.1	2	6	0.9	11	0	3	1.5	0	0.3	2	64
MM96-01 5	296	3	55	9.3	7	94	2067	6.6	39	5	10	2	171	0.9	4	2	30	4.7	0	4	55	1	35	0	3	1.1	0	0.1	2	10920
MM96-01 1	22	16	9	0.7	11	30	418	4.99	52	5	ND	2	9	0.2	2	2	31	0.3	0.1	3	15	0.3	42	0.2	7	1.1	0	0.4	2	56
MM96-01 11	1494	3	9	2.2	5	59	1894	3.62	52	5	ND	2	17	0.3	2	3	11	1.8	0	4	124	0.2	50	0	3	0.4	0	0.1	2	120
MM96-01 6	40780	4	10	19.7	5	30	483	9.54	14	5	8	2	4	0.2	7	16	9	0.2	0	2	57	0.1	15	0	3	0.3	0	0.1	2	8890
MM96-01 13	16630	4	26	11.2	4	13	675	6.17	26	5	9	3	4	0.2	2	8	21	0.2	0.1	5	57	0.4	59	0	3	1.4	0	0.2	2	10820
MM96-01 3	2889	5	60	2.4	55	37	1137	7.78	26	5	ND	2	36	0.6	2	2	178	2.8	0.1	5	49	2.1	22	0.1	3	2.5	0	0.1	2	180
MM96-02 3	373	11	60	2.4	3	20	698	7.6	40	5	ND	2	44	0.3	2	2	39	0.9	0.1	3	66	0.7	23	0.1	3	1.9	0.1	0.1	2	62
MM96-02 1	54	7	20	0.3	5	16	545	3.53	31	5	ND	2	10	0.2	2	2	43	0.5	0.1	3	23	0.6	48	0.1	3	0.8	0	0.2	2	16
MM96-02 22	31	13	67	2.9	5	74	1005	8.42	14	5	ND	2	4	0.4	2	2	30	0.1	0.1	2	38	0.7	38	0	3	1.2	0	0.2	2	43
MM96-02 6	26	3	9	0.3	4	30	438	3.57	22	5	ND	2	6	0.2	2	2	24	0.1	0.1	2	42	0.3	163	0	3	0.9	0	0.2	27	18
MM96-02 16	1200	3	49	0.6	10	18	305	3.87	2	5	ND	2	21	0.7	2	2	106	1.9	0.1	5	51	0.8	39	0.1	3	2.1	0.1	0.2	2	49
MM96-02 6	39	3	55	0.3	3	61	1454	18.43	330	5	ND	3	4	0.2	2	2	71	0.2	0.1	3	26	1.7	26	0.1	3	3.8	0	0.2	2	760
MM96-02 5	29	3	75	0.3	4	66	1845	14.39	358	5	ND	3	4	0.2	2	2	76	0.2	0.1	7	33	2.2	32	0	3	4.1	0	0.2	2	1560
MM96-02 3	210	13	46	0.6	3	11	655	8.36	20	5	ND	6	5	0.4	2	2	91	0.3	0.1	5	26	1.6	48	0	3	2.8	0	0.2	2	50
MM96-02 3	327	3	29	0.4	13	19	942	4.69	15	5	ND	2	18	0.3	2	2	97	0.5	0.1	6	90	0.8	48	0.1	3	1.8	0	0.1	2	30
MM96-02 9	7417	6	126	9	25	73	254	5.42	17	5	ND	2	13	2.8	2	2	299	0.8	0.1	5	25	0.6	36	0.1	3	1.1	0	0.1	2	2050
MM96-03 7	6056	3	25	7.4	10	32	563	3.01	35	5	ND	2	20	0.3	2	4	14	2.2	0	2	94	0.2	29	0	3	0.4	0	0.1	2	160
MM96-03 3	3516	13	130	5.8	17	35	1046	4.72	27	5	ND	2	70	3.5	2	3	212	2.6	0.2	9	41	2.2	40	0.1	3	2.2	0	0.1	2	120
MM96-03 3	890	3	46	3.5	18	39	6101	4.74	67	5	ND	2	252	0.8	5	2	65	24	0	12	50	0.9	19	0	3	1.4	0	0.1	2	160
MM96-03 162	35298	1538	1449	50.8	73	101	688	15.76	192	5	12	2	24	83	26	2	262	1.5	0.4	6	21	2.4	8	0	3	2.9	0	0.2	2	13580
MM96-03 47	950	71	106	4.8	144	131	595	18.69	42	5	ND	2	4	0.4	10	2	240	0.2	0.1	1	173	2.2	9	0	3	3.1	0	0.1	2	130

G E O C H E M I C A L A N A L Y S I S C E R T I F I C A T E

TEUTON RESOURCES CORP.

Project: Clone

Sample Type: Rocks

Multi-element ICP Analysis - .500 gram sample is digested with 3 ml of aqua regia, diluted to 10 ml with water. This leach is partial for Mn, Fe, Ca, P, La, Cr, Mg, Ba, Ti, B, W and limited for Na, K and Al. Detection Limit for Au is 3 ppm.
 *Au Analysis- 10 gram sample is digested with aqua regia, MIBK extracted, graphite furnace AA finished to 1 ppb detection.

Analyst RSam
 Report No. 9621838
 Date: August 17, 1996

ELEMENT SAMPLE	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
D96-156	84	59	25	35	1.9	27	17	79	6.06	18	5	ND	2	21	.2	2	2	24	.11	.022	6	80	.13	13	.01	3	.46	.06	.27	2	14
D96-157	2	161	5	51	.3	8	20	760	5.97	2	5	ND	2	34	.2	2	2	230	1.59	.144	4	25	2.12	19	.23	16	2.16	.05	.06	2	14
D96-158	2	193	24	38	.3	18	42	387	9.38	8	5	ND	2	28	.2	2	2	53	.53	.145	4	17	1.33	18	.01	3	1.90	.02	.39	2	34
D96-159	3	113	15	29	.3	3	14	319	7.19	4	5	ND	2	24	.2	2	2	124	.42	.162	3	18	1.11	36	.12	4	1.43	.07	.29	2	14
MM96-035	2	154	3	31	.3	6	19	680	6.73	17	5	ND	2	46	.2	4	2	209	2.06	.172	5	16	2.24	25	.25	3	2.06	.05	.13	2	28
MM96-036	3	14	3	28	.3	7	14	1701	3.92	2	5	ND	2	871	.2	2	2	130	11.02	.001	3	66	1.56	21	.01	3	1.84	.01	.02	2	7
MM96-037	15	155	30	78	.3	14	30	478	6.72	11	5	ND	2	32	.5	5	2	127	1.35	.151	3	18	.93	30	.19	3	1.16	.04	.26	2	17
MM96-038	2	8	3	22	.3	8	19	2884	5.74	2	5	ND	2	469	.2	2	2	16	18.60	.001	2	58	3.66	36	.01	3	.21	.01	.06	2	12

G E O C H E M I C A L A N A L Y S I S C E R T I F I C A T E

TEUTON RESOURCES CORP.

Project: Clone

Sample Type: Rocks

Multi-element ICP Analysis - .500 gram sample is digested with 3 ml of aqua regia, diluted to 10 ml with water. This leach is partial for Mn, Fe, Ca, P, La, Cr, Mg, Ba, Ti, B, W and limited for Na, K and Al. Detection Limit for Au is 3 ppm.
*Au Analysis- 10 gram sample is digested with aqua regia, MIBK extracted, graphite furnace AA finished to 1 ppb detection.

Analyst RSam
Report No. 9621838
Date: August 17, 1996

ELEMENT SAMPLE	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
D96-156	84	59	25	35	1.9	27	17	79	6.06	18	5	ND	2	21	.2	2	2	24	.11	.022	6	80	.13	13	.01	3	.46	.06	.27	2	14
D96-157	2	161	5	51	.3	8	20	760	5.97	2	5	ND	2	34	.2	2	2	230	1.59	.144	4	25	2.12	19	.23	16	2.16	.05	.06	2	14
D96-158	2	193	24	38	.3	18	42	387	9.38	8	5	ND	2	28	.2	2	2	53	.53	.145	4	17	1.33	18	.01	3	1.90	.02	.39	2	34
D96-159	3	113	15	29	.3	3	14	319	7.19	4	5	ND	2	24	.2	2	2	124	.42	.162	3	18	1.11	36	.12	4	1.43	.07	.29	2	14
MM96-035	2	154	3	31	.3	6	19	680	6.73	17	5	ND	2	46	.2	4	2	209	2.06	.172	5	16	2.24	25	.25	3	2.06	.05	.13	2	28
MM96-036	3	14	3	28	.3	7	14	1701	3.92	2	5	ND	2	871	.2	2	2	130	11.02	.001	3	66	1.56	21	.01	3	1.84	.01	.02	2	7
MM96-037	15	155	30	78	.3	14	30	478	6.72	11	5	ND	2	32	.5	5	2	127	1.35	.151	3	18	.93	30	.19	3	1.16	.04	.26	2	17
MM96-038	2	8	3	22	.3	8	19	2884	5.74	2	5	ND	2	469	.2	2	2	16	18.60	.001	2	58	3.66	36	.01	3	.21	.01	.06	2	12



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5129

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

18-Sep-96

ATTENTION: DINO CREMONESE

No. of samples received: 16
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: NONE GIVEN
P.O.#: NONE GIVEN
Samples submitted by: DAVID HICK

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	As (%)	Co (%)
1	D96-160	15.32	0.447	-	-	-	-
2	D96-161	2.73	0.080	-	-	5.05	0.080
3	D96-162	5.90	0.172	-	-	-	-
4	D96-163	9.89	0.288	-	-	2.56	-
5	D96-164	4.28	0.125	-	-	-	-
6	D96-165	14.56	0.425	-	-	5.08	-
7	D96-166	16.66	0.486	-	-	-	-
8	D96-167	1.61	0.047	-	-	-	-
9	D96-168	9.87	0.288	29.2	0.85	1.37	-

QC/DATA:


Resplit:

1	D96-160	15.22	0.444	-	-	-	-
---	---------	-------	-------	---	---	---	---

Standard:

CD-1	-	-	-	-	-	0.66	-
Su1a	-	-	-	-	-	-	0.042

XLS/96Teuton#8


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

14-Aug-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5129

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 16
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: NONE GIVEN
P.O.#: NONE GIVEN
Samples submitted by: DAVID HICK

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	D96-160	>1000	6.6	0.35	1110	45	10	0.69	<1	45	145	84	>10	<10	0.08	156	9	<0.01	8	130	10	<5	<20	8	<0.01	20	8	<10	<1	7
2	D96-161	>1000	5.8	3.52	>10000	75	<5	2.40	<1	782	124	540	>10	<10	2.35	885	13	<0.01	21	1010	56	<5	<20	59	0.02	<10	146	<10	<1	30
3	D96-162	>1000	4.6	0.50	185	45	<5	0.27	<1	15	142	3329	3.59	<10	0.18	129	5	<0.01	5	540	6	<5	<20	5	<0.01	10	8	<10	<1	8
4	D96-163	>1000	3.8	2.44	>10000	100	<5	3.28	<1	121	60	1106	>10	<10	1.29	756	12	<0.01	5	1730	16	<5	<20	57	<0.01	<10	108	<10	<1	23
5	D96-164	>1000	9.0	0.57	665	60	<5	0.13	<1	15	85	1713	>10	<10	0.25	192	14	<0.01	11	90	18	<5	<20	2	<0.01	40	16	<10	<1	22
6	D96-165	>1000	6.0	0.26	>10000	60	<5	0.04	<1	110	54	719	>10	<10	0.07	98	16	<0.01	17	200	4	<5	<20	14	<0.01	50	7	<10	<1	8
7	D96-166	>1000	16.6	1.91	1330	55	<5	0.26	<1	24	101	3166	>10	<10	1.05	272	10	<0.01	21	1060	20	<5	<20	6	<0.01	30	69	<10	<1	22
8	D96-167	>1000	7.2	1.68	1160	125	<5	3.78	<1	47	96	1022	>10	<10	1.06	1109	16	<0.01	32	750	24	<5	<20	69	<0.01	10	53	<10	<1	26
9	D96-168	>1000	>30	0.39	>10000	40	<5	6.79	<1	46	99	8634	>10	<10	0.13	1514	10	<0.01	14	<10	4	<5	<20	61	<0.01	<10	9	10	<1	30
10	MM96-039	310	0.8	2.05	110	190	<5	4.70	<1	16	126	84	4.35	<10	1.49	964	7	0.02	18	1450	40	<5	<20	157	<0.01	<10	97	<10	2	87
11	MM96-040	10	0.8	1.50	50	245	<5	7.79	<1	28	40	231	7.41	<10	1.78	1642	5	0.03	17	3200	14	<5	<20	244	0.01	<10	126	<10	9	90
12	MM96-041	230	1.0	1.41	305	75	10	0.36	<1	18	125	23	6.05	<10	0.44	180	32	<0.01	13	1140	26	<5	<20	7	<0.01	10	39	<10	<1	18
13	MM96-042	5	<0.2	3.19	10	75	5	0.90	<1	26	64	89	6.90	<10	2.60	1133	<1	0.05	14	1690	28	<5	<20	42	0.24	<10	218	<10	4	68
14	MM96-043	5	<0.2	2.72	<5	65	5	1.94	1	32	90	77	7.93	<10	2.67	1178	<1	0.04	17	1800	16	<5	<20	34	0.31	<10	302	<10	4	82
15	MM96-044	5	<0.2	2.58	<5	55	<5	1.08	<1	42	39	168	7.44	<10	2.08	641	<1	0.07	16	2390	22	<5	<20	49	0.28	<10	411	<10	4	59
16	MM96-045	20	<0.2	2.65	<5	65	<5	0.91	<1	40	59	397	7.14	<10	2.69	772	<1	0.07	14	2310	26	<5	<20	40	0.27	<10	347	<10	4	48

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
QC/DATA:																															
Resplit:																															
1	D96-160	>1000	6.0	0.32	1115	50	15	0.68	<1	44	120	82	>10	<10	0.08	144	13	<0.01	6	130	6	<5	<20	10	<0.01	20	7	<10	<1	6	
Repeat:																															
1	D96-160	>1000	6.4	0.36	1125	55	15	0.69	<1	45	146	86	>10	<10	0.09	159	9	<0.01	7	120	6	<5	<20	10	<0.01	20	8	<10	<1	6	
10	MM96-039	-	0.8	2.05	110	185	<5	4.71	<1	16	126	83	4.36	<10	1.49	968	6	0.02	19	1450	40	<5	<20	157	<0.01	<10	98	<10	2	89	
Standard:																															
GEO 96		145	1.2	1.91	60	165	<5	1.92	<1	20	66	83	4.39	<10	1.02	743	<1	0.02	20	800	20	<5	<20	60	0.13	<10	84	<10	5	73	

df/5128r
XLS/96Teuton#3


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

13-Aug-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5135

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 25

Sample Type: ROCK

PROJECT #: CLONE

SHIPMENT #: 27

P.O.#: NONE GIVEN

Samples submitted by: R. MCLEOD


Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Br	Ti %	U	V	W	Y	Zn
1	RJM96-01	680	2.0	3.18	<5	260	60	1.62	<1	33	33	54	>10	20	1.12	1363	13	<0.01	<1	1510	60	<5	<20	49	0.08	<10	237	<10	<1	84
2	RJM96-02	145	0.8	3.99	<5	275	<5	1.31	<1	65	19	275	>10	<10	1.57	1631	9	<0.01	6	1860	84	<5	<20	52	0.04	<10	169	<10	<1	104
3	RJM96-03	20	0.6	4.04	<5	415	10	1.32	<1	78	22	109	9.99	<10	1.92	1509	6	<0.01	6	1220	34	<5	<20	57	0.02	<10	105	<10	<1	110
4	RJM96-04	5	0.4	4.60	<5	345	10	0.62	<1	84	18	62	9.03	<10	3.04	1378	6	<0.01	9	1560	42	<5	<20	16	<0.01	<10	148	<10	<1	159
5	RJM96-05	85	2.8	2.73	<5	380	25	1.71	1	43	21	108	>10	<10	1.42	1003	9	<0.01	4	1180	82	<5	<20	56	0.05	<10	134	<10	<1	118
6	RJM96-06	5	0.8	5.08	<5	425	<5	1.86	<1	51	85	213	9.01	<10	3.43	1632	6	<0.01	14	1600	74	<5	<20	40	<0.01	<10	226	<10	<1	262
7	RJM96-07	5	0.4	3.27	20	425	<5	5.66	1	24	34	92	6.63	<10	1.34	1884	7	<0.01	13	1680	26	<5	<20	96	<0.01	<10	90	<10	<1	87
8	RJM96-08	30	1.4	3.45	35	175	10	5.17	<1	21	30	89	7.29	<10	1.64	1693	8	<0.01	6	1740	56	<5	<20	69	<0.01	<10	83	<10	2	178
9	RJM96-09	95	3.0	3.05	40	135	<5	2.92	1	31	25	316	7.18	<10	1.26	1169	8	<0.01	5	1870	132	<5	<20	47	<0.01	<10	81	<10	<1	345
10	RJM96-10	80	0.6	4.07	10	200	10	3.82	3	62	36	45	8.49	<10	2.33	2020	5	<0.01	13	1510	84	<5	<20	60	<0.01	<10	163	<10	<1	627
11	RJM96-11	130	1.0	4.44	5	335	<5	5.13	9	56	31	192	9.20	<10	2.65	2532	8	<0.01	14	1610	122	<5	<20	97	<0.01	<10	203	<10	<1	344
12	RJM96-12	60	0.8	4.72	40	210	<5	2.08	3	44	30	208	9.92	<10	2.89	1881	15	<0.01	11	1580	182	<5	<20	36	<0.01	<10	201	<10	<1	401
13	RJM96-13	125	2.0	4.50	265	100	<5	0.44	<1	38	31	272	>10	<10	2.78	1699	30	<0.01	9	1750	376	<5	<20	33	<0.01	<10	183	<10	<1	472
14	RJM96-14	5	1.0	4.73	15	240	<5	2.08	2	33	20	291	9.24	<10	2.91	2027	9	0.01	8	1550	188	<5	<20	26	<0.01	<10	149	<10	<1	365
15	RJM96-15	90	1.2	4.87	55	200	5	1.17	1	55	21	157	>10	<10	2.92	1747	7	<0.01	9	1470	102	<5	<20	19	<0.01	<10	136	<10	<1	403
16	RJM96-16	25	0.4	4.32	<5	365	5	5.17	<1	26	11	43	8.58	<10	2.72	1914	5	0.01	6	1270	42	<5	<20	171	<0.01	<10	121	<10	<1	132
17	RJM96-17	5	2.4	1.92	70	65	<5	0.43	<1	32	21	140	6.75	<10	0.83	505	9	<0.01	10	1710	32	<5	<20	6	<0.01	<10	56	<10	<1	46
18	RJM96-18	5	0.6	1.58	25	125	<5	1.53	<1	14	32	17	3.17	<10	0.78	604	4	<0.01	4	1430	20	<5	<20	35	<0.01	<10	25	<10	<1	31
19	RJM96-19	5	1.8	2.47	70	95	15	1.40	<1	29	15	79	6.54	<10	1.29	961	7	<0.01	8	1630	32	<5	<20	34	<0.01	<10	55	<10	<1	58
20	RJM96-20	10	2.2	2.12	80	90	<5	2.32	<1	31	22	111	7.06	<10	0.62	1396	11	<0.01	9	1690	32	<5	<20	44	<0.01	<10	60	<10	<1	61
21	RJM96-21	5	2.2	2.59	30	85	<5	1.27	<1	25	26	84	7.25	<10	1.44	1972	7	<0.01	11	1940	40	<5	<20	24	<0.01	<10	86	<10	<1	56
22	RJM96-22	10	2.4	2.41	80	70	<5	1.62	<1	29	31	144	6.92	<10	1.14	939	11	<0.01	11	1670	40	<5	<20	22	<0.01	<10	77	<10	<1	109
23	RJM96-23	15	2.2	2.89	80	90	5	6.37	10	31	28	105	7.86	<10	1.57	2197	11	<0.01	16	1920	114	<5	<20	110	<0.01	<10	73	<10	<1	545
24	RJM96-24	205	6.0	3.07	1040	135	<5	0.43	<1	49	25	417	>10	<10	1.25	476	85	<0.01	10	1880	216	<5	<20	4	<0.01	20	81	<10	<1	354
25	RJM96-25	260	4.8	0.89	25	475	40	1.66	2	13	21	62	>10	<10	0.23	517	12	<0.01	1	760	92	<5	<20	55	0.11	<10	140	<10	<1	28

08/14/96 16:29 604 573 4557 ECO-TECH KAM.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
QC/DATA:																															
Resplit:																															
1	RJM96-01	600	1.8	3.11	<5	255	50	1.72	1	33	35	55	>10	20	1.08	1345	14	<0.01	<1	1490	64	<5	<20	44	0.08	<10	234	<10	<1	85	
Repeat:																															
1	RJM96-01	660	2.0	3.26	<5	280	55	1.63	<1	33	33	55	>10	30	1.13	1365	11	<0.01	<1	1550	62	<5	<20	48	0.08	<10	242	<10	<1	85	
10	RJM96-10	-	0.6	4.17	20	210	10	3.73	3	63	37	46	8.65	<10	2.36	2055	5	<0.01	16	1610	90	<5	<20	67	<0.01	<10	168	<10	<1	651	
20	RJM96-20	5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Standard:																															
GEO 96		145	1.2	1.94	65	165	<5	1.93	<1	20	67	83	4.41	<10	1.05	751	<1	0.02	20	810	20	<5	<20	61	0.13	<10	88	<10	3	74	
GEO 96		140	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	

dl/5132ar
XLS/96Teuton#3


ECO-TECH LABORATORIES LTD.
Frank J. Pezzoffi, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AS 96-5136

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

15-Aug-96

ATTENTION: DINO CREMONESE

No. of samples received: 50
Sample Type: CORE
PROJECT #: CLONE
SHIPMENT #: 27
P.O.#: NONE GIVEN
Samples submitted by: R.MCLEOD

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	ERK-96-26	5.34	0.156
30	ERK-96-30	1.32	0.038

XLS/96Teuton#4

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

15-Aug-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5136

TEUTON RESOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 50
Sample Type: CORE
PROJECT #: CLONE
SHIPMENT #: 27
P.O. #: NONE GIVEN
Samples submitted by: R. MCLEOD

Values in ppm unless otherwise reported

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	ERK-98-01	5	0.4	2.32	<5	255	<5	8.83	9	20	20	25	8.80	<10	1.11	1357	5	<0.01	7	1540	6	<5	<20	165	0.03	<10	87	<10	1	303
2	ERK-98-02	15	0.2	2.23	<5	230	<5	8.33	3	24	13	22	6.52	<10	0.88	1717	4	<0.01	6	1250	10	<5	<20	145	0.04	<10	64	<10	2	115
3	ERK-98-03	5	<0.2	2.94	<5	305	<5	5.87	<1	23	17	29	6.25	<10	1.48	1354	4	<0.01	5	1340	6	<5	<20	117	0.02	<10	71	<10	<1	124
4	ERK-98-04	10	<0.2	2.78	<5	1070	5	6.11	1	14	9	19	5.66	<10	1.80	1397	4	<0.01	4	1210	4	<5	<20	181	0.01	<10	58	<10	<1	104
5	ERK-98-05	5	<0.2	3.40	<5	605	15	3.59	<1	31	9	5	7.58	<10	1.94	1150	5	<0.01	7	1380	2	<5	<20	91	0.02	<10	74	<10	<1	105
6	ERK-98-06	55	0.4	3.46	<5	385	10	3.81	1	28	20	25	8.40	<10	2.12	1151	5	<0.01	8	1610	8	<5	<20	111	0.03	<10	114	<10	<1	91
7	ERK-98-07	385	0.6	3.70	5	190	<5	2.73	<1	33	22	61	7.80	<10	2.68	1096	5	<0.01	7	1210	10	<5	<20	84	0.01	<10	156	<10	<1	91
8	ERK-98-08	10	2.8	4.22	<5	160	<5	3.39	1	30	31	2033	8.25	<10	2.91	1488	9	<0.01	8	1230	10	<5	<20	92	0.01	<10	124	<10	<1	103
9	ERK-98-09	225	0.2	4.69	<5	135	<5	4.00	2	20	29	153	9.28	<10	3.25	1516	7	<0.01	11	1290	4	<5	<20	99	0.01	<10	140	<10	<1	222
10	ERK-98-10	50	<0.2	4.54	5	120	5	3.25	1	20	38	57	8.73	<10	3.44	1290	6	<0.01	11	1480	8	<5	<20	70	<0.01	<10	135	<10	<1	125
11	ERK-98-11	40	<0.2	4.05	10	415	<5	3.80	1	17	34	41	7.60	<10	2.99	1209	6	<0.01	12	1220	72	<5	<20	90	<0.01	<10	129	<10	<1	98
12	ERK-98-12	475	0.4	4.34	50	135	10	1.25	<1	23	36	18	9.54	<10	2.90	1341	8	<0.01	10	1070	24	<5	<20	28	<0.01	<10	129	<10	<1	160
13	ERK-98-13	25	<0.2	4.10	50	155	15	4.09	<1	22	31	19	7.46	<10	2.66	1429	6	<0.01	10	1270	2	<5	<20	96	0.01	<10	106	<10	<1	91
14	ERK-98-14	5	<0.2	4.24	15	190	10	5.83	<1	18	23	10	7.82	<10	3.04	1708	5	<0.01	8	1140	<2	<5	<20	161	<0.01	<10	100	<10	<1	81
15	ERK-98-15	5	<0.2	4.15	<5	300	10	6.50	<1	17	24	5	7.05	<10	2.80	1593	5	<0.01	8	1190	<2	<5	<20	166	0.01	<10	102	<10	<1	77
16	ERK-98-16	175	0.2	4.09	15	225	5	6.08	<1	24	26	35	7.59	<10	2.49	1747	7	<0.01	9	1250	8	<5	<20	138	0.01	<10	93	<10	<1	77
17	ERK-98-17	5	0.4	4.06	5	265	10	5.03	<1	25	10	47	7.44	<10	2.48	1685	5	<0.01	6	1820	<2	<5	<20	110	0.01	<10	85	<10	<1	59
18	ERK-98-18	760	1.8	3.32	90	210	<5	1.93	<1	19	23	67	7.00	<10	1.94	1017	16	<0.01	5	1710	14	<5	<20	34	<0.01	<10	72	<10	<1	50
19	ERK-98-19	5	<0.2	3.17	<5	315	10	2.45	<1	17	17	8	6.43	<10	1.75	1066	5	<0.01	8	1780	4	<5	<20	48	<0.01	<10	65	<10	<1	46
20	ERK-98-20	5	1.2	2.70	20	140	<5	4.43	3	14	34	120	5.32	<10	2.31	1586	4	0.03	9	2000	70	<5	<20	134	<0.01	<10	121	<10	<1	247
21	ERK-98-21	5	2.2	3.17	85	130	<5	3.01	6	21	19	194	8.03	<10	2.27	1643	8	0.01	10	2260	40	<5	<20	88	0.01	<10	162	<10	<1	306
22	ERK-98-22	10	2.2	3.12	90	120	<5	3.10	5	22	14	199	8.03	<10	2.27	1683	8	0.01	12	2280	42	<5	<20	89	<0.01	<10	161	<10	<1	277
23	ERK-98-23	75	4.2	3.94	50	115	<5	0.88	2	33	13	390	>10	<10	2.85	1401	16	<0.01	10	2360	42	<5	<20	21	<0.01	<10	228	<10	<1	202
24	ERK-98-24	180	6.2	3.96	140	110	<5	2.19	2	59	22	844	>10	<10	2.84	1654	12	<0.01	10	2130	46	<5	<20	47	0.01	<10	225	<10	<1	205
25	ERK-98-25	90	6.0	3.23	615	100	<5	4.89	4	42	17	416	>10	<10	2.17	2001	9	0.01	10	2130	50	<5	<20	91	0.01	<10	167	<10	<1	330

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS-5136

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	ERK-98-26	>1000	8.0	3.47	135	110	<5	1.37	9	45	18	444	>10	<10	2.24	1744	66	<0.01	12	2310	94	<5	<20	28	0.01	<10	202	<10	<1	380
27	ERK-98-27	50	4.6	3.10	105	100	<5	2.62	1	37	18	444	>10	<10	2.01	1673	12	<0.01	13	2220	42	<5	<20	58	<0.01	<10	135	<10	<1	189
28	ERK-98-28	40	3.8	3.36	80	110	<5	3.30	1	31	21	298	>10	<10	2.37	1856	11	<0.01	13	2100	34	<5	<20	82	0.01	<10	150	<10	<1	181
29	ERK-98-29	80	3.6	3.38	130	110	<5	5.84	11	24	22	314	9.56	<10	2.70	2139	8	0.01	11	1860	30	<5	<20	147	0.01	<10	153	<10	<1	414
30	ERK-98-30	>1000	10.8	2.88	210	75	15	1.10	<1	57	42	323	>10	<10	1.68	1476	25	<0.01	4	690	410	<5	<20	17	<0.01	<10	97	<10	<1	237
31	ERK-98-31	5	0.8	4.14	<5	300	10	4.27	<1	12	9	9	8.19	<10	3.03	1540	7	0.03	3	1260	8	<5	<20	163	0.01	<10	157	<10	<1	113
32	ERK-98-32	145	0.2	2.90	20	95	10	4.00	21	26	24	27	6.63	<10	2.30	1153	10	0.02	3	1120	20	<5	<20	133	<0.01	<10	138	<10	<1	782
33	ERK-98-33	5	<0.2	3.58	<5	345	10	2.52	<1	9	13	2	7.69	<10	2.77	1161	6	0.02	2	1200	<2	<5	<20	87	<0.01	<10	161	<10	<1	95
34	ERK-98-34	5	<0.2	3.66	<5	200	10	3.27	<1	15	17	3	7.92	<10	2.71	1180	5	0.03	3	1330	<2	<5	<20	96	0.01	<10	141	<10	<1	92
35	ERK-98-35	5	<0.2	3.33	<5	240	5	2.61	<1	20	10	42	7.48	<10	2.39	1168	5	0.02	2	1380	4	<5	<20	73	<0.01	<10	128	<10	<1	81
36	ERK-98-36	205	1.8	2.67	50	90	<5	3.10	5	50	22	202	7.18	<10	2.17	1135	10	<0.01	5	1170	38	<5	<20	63	<0.01	<10	128	<10	<1	321
37	ERK-98-37	35	1.0	3.82	35	145	<5	3.94	<1	21	17	85	7.28	<10	3.47	1513	8	<0.01	5	1440	6	<5	<20	73	<0.01	<10	117	<10	<1	125
38	ERK-98-38	5	<0.2	3.96	<5	205	10	6.17	<1	13	8	8	7.25	<10	2.97	1869	5	0.01	5	1520	<2	<5	<20	131	<0.01	<10	119	<10	<1	122
39	ERK-98-39	5	<0.2	4.35	<5	255	15	4.37	<1	13	7	31	7.86	<10	3.06	1812	5	0.02	4	1700	<2	<5	<20	112	0.01	<10	134	<10	<1	147
40	ERK-98-40	5	<0.2	3.42	5	205	<5	4.06	<1	13	11	80	6.51	<10	2.12	1427	4	0.01	5	1710	4	<5	<20	82	<0.01	<10	115	<10	<1	106
41	ERK-98-41	95	3.4	3.59	85	130	<5	6.97	2	57	27	327	8.99	<10	3.08	1840	9	0.01	9	1180	24	<5	<20	127	<0.01	<10	116	<10	<1	138
42	ERK-98-42	75	4.2	2.95	80	95	<5	6.49	17	43	30	399	7.90	<10	2.61	1788	16	<0.01	8	1170	78	<5	<20	152	<0.01	<10	92	<10	<1	478
43	ERK-98-43	5	2.2	4.21	35	95	<5	3.32	9	72	39	588	>10	<10	3.78	1523	10	0.02	9	1400	72	<5	<20	59	<0.01	<10	171	<10	<1	365
44	ERK-98-44	110	4.6	4.04	50	110	<5	4.28	3	58	30	668	>10	<10	3.04	1633	15	<0.01	11	1300	40	<5	<20	69	<0.01	<10	135	<10	<1	305
45	ERK-98-45	75	3.4	4.30	20	170	<5	2.30	1	28	27	278	9.64	<10	2.63	1449	16	<0.01	11	1150	100	<5	<20	47	<0.01	<10	119	<10	<1	425
46	ERK-98-46	35	1.8	3.54	45	115	<5	2.30	1	41	19	206	9.53	<10	3.07	1168	9	0.01	8	1510	36	<5	<20	55	<0.01	<10	136	<10	<1	161
47	ERK-98-47	30	1.6	3.20	55	80	<5	5.01	<1	37	18	326	9.78	<10	2.98	1217	7	0.02	8	1320	20	<5	<20	119	<0.01	<10	156	<10	<1	122
48	ERK-98-48	50	1.4	4.40	90	90	<5	4.69	<1	17	27	141	8.89	<10	4.42	1434	7	0.02	8	1430	24	<5	<20	128	<0.01	<10	201	<10	<1	83
49	ERK-98-49	5	1.4	4.41	100	135	<5	4.65	<1	16	27	141	8.72	<10	4.29	1409	6	0.04	8	1430	28	<5	<20	125	0.01	<10	200	<10	<1	88
50	ERK-98-50	5	0.8	3.92	45	75	<5	3.06	1	24	22	190	8.73	<10	3.46	1338	6	0.02	8	1360	28	<5	<20	78	<0.01	<10	189	<10	<1	106

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS-5138

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
------	-------	---------	----	------	----	----	----	------	----	----	----	----	------	----	------	----	----	------	----	---	----	----	----	----	------	---	---	---	---	----

14-Aug-98

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5137

TEUTON RESOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 804-573-5700
Fax : 804-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 28
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-027
P.O.#: NONE GIVEN
Samples submitted by: R.MCLEOD

Values in ppm unless otherwise reported

Et.#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	D96-134	5	0.2	0.91	<5	1185	<5	3.33	4	2	24	44	3.89	<10	0.21	608	2	<0.01	3	1630	28	<5	<20	85	0.03	<10	42	<10	<1	67
2	D96-135	65	1.8	1.67	<5	930	<5	2.61	3	13	12	318	6.67	<10	0.41	607	4	<0.01	7	1500	36	<5	<20	56	0.06	<10	70	<10	<1	172
3	D96-136	80	4.0	1.50	<5	700	<5	2.41	9	18	9	906	5.87	<10	0.37	734	11	<0.01	6	1530	590	<5	<20	39	0.05	<10	61	<10	<1	227
4	D96-137	60	0.4	1.68	<5	395	10	4.14	7	19	8	13	6.70	<10	0.41	714	3	<0.01	4	1690	56	<5	<20	70	0.05	<10	58	<10	<1	207
5	D96-138	15	<0.2	1.59	<5	640	<5	4.47	<1	10	10	9	4.22	<10	0.55	650	2	<0.01	4	1850	22	<5	<20	84	0.03	<10	56	<10	<1	82
6	D96-139	10	3.0	0.59	<5	680	<5	7.34	6	1	25	1053	4.25	<10	0.13	699	3	<0.01	3	1150	104	<5	<20	129	0.02	<10	39	<10	<1	11
7	D96-140	5	0.4	3.34	<5	315	<5	5.82	4	28	8	84	6.21	<10	2.05	1205	4	<0.01	5	1760	4	<5	<20	118	0.02	<10	85	<10	<1	250
8	D96-141	40	1.4	3.98	<5	275	<5	5.49	4	31	13	24	6.98	<10	2.20	1276	4	<0.01	8	1710	4	<5	<20	97	0.02	<10	95	<10	<1	240
9	D96-142	5	0.2	3.76	<5	930	10	7.93	5	21	13	19	6.27	<10	2.01	1514	4	<0.01	9	1680	6	<5	<20	149	0.02	<10	96	<10	1	223
10	D96-143	160	0.4	3.60	<5	215	10	7.88	2	22	10	30	6.67	<10	1.84	1541	5	<0.01	7	1540	4	<5	<20	134	0.02	<10	91	<10	<1	142
11	D96-144	110	0.4	3.24	<5	195	15	5.83	2	18	7	5	9.04	<10	1.14	1189	7	<0.01	6	1430	4	<5	<20	89	0.04	<10	84	<10	<1	98
12	D96-145	40	<0.2	3.21	<5	330	5	6.33	2	18	5	9	8.92	<10	1.21	1265	5	<0.01	5	1190	2	<5	<20	114	0.05	<10	84	<10	<1	95
13	D96-146	10	<0.2	4.24	<5	285	10	5.62	<1	29	14	4	7.82	<10	2.33	1451	4	<0.01	10	1640	<2	<5	<20	135	0.02	<10	99	<10	<1	128
14	D96-147	45	<0.2	3.88	<5	550	10	3.69	<1	26	15	21	7.54	<10	2.05	1253	5	<0.01	10	1600	2	<5	<20	100	0.02	<10	93	<10	<1	130
15	D96-148	110	<0.2	3.64	<5	180	<5	5.81	<1	17	23	3	7.26	<10	2.34	1250	4	<0.01	8	1370	<2	<5	<20	194	0.01	<10	121	<10	<1	122
16	D96-149	90	<0.2	4.30	<5	260	<5	4.76	<1	22	19	231	9.27	<10	2.83	1459	9	0.01	6	1300	8	<5	<20	165	0.02	<10	144	<10	<1	127
17	D96-150	130	3.4	3.77	80	185	<5	1.81	<1	41	4	1953	>10	<10	1.75	1003	18	<0.01	7	1290	40	<5	<20	37	0.01	<10	80	<10	<1	97
18	D96-151	290	3.4	3.83	485	150	10	3.02	<1	34	16	39	>10	<10	2.22	1311	99	<0.01	6	1250	56	<5	<20	73	0.01	<10	99	<10	<1	153
19	D96-152	120	0.4	4.13	40	185	5	5.68	2	22	16	34	8.15	<10	2.68	1222	7	<0.01	6	1320	20	<5	<20	210	0.01	<10	113	<10	<1	102
20	D96-153	130	3.6	4.05	<5	280	<5	5.56	<1	23	26	148	7.37	<10	2.47	1334	5	<0.01	8	1220	10	<5	<20	209	0.02	<10	102	<10	<1	93
21	D96-154	10	<0.2	3.83	<5	350	5	6.44	<1	18	16	3	6.20	<10	2.61	1642	3	<0.01	4	1260	6	<5	<20	180	0.02	<10	92	<10	<1	73
22	D96-155	5	<0.2	3.68	65	225	10	6.40	<1	21	8	3	6.92	<10	2.31	1485	5	<0.01	4	1350	20	<5	<20	189	0.02	<10	85	<10	<1	80
23	D96-169	90	7.8	3.18	160	120	<5	5.85	1	41	20	312	9.26	<10	2.30	1387	14	<0.01	9	1630	50	<5	<20	100	0.01	<10	82	<10	<1	185
24	D96-170	115	11.0	3.99	205	120	<5	2.31	1	35	18	191	9.12	<10	3.48	915	11	<0.01	7	1850	96	<5	<20	34	0.01	<10	116	<10	<1	203
25	D96-171	130	11.8	3.35	160	115	<5	1.50	4	30	28	196	6.31	<10	2.69	750	13	<0.01	9	1530	102	<5	<20	21	0.01	<10	125	<10	<1	346

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS-5137

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	D96-172	110	9.0	3.03	190	105	<5	1.64	2	34	30	280	9.47	<10	2.24	979	9	<0.01	11	1850	54	<5	<20	28	<0.01	<10	146	<10	<1	200
27	D96-173	125	6.8	2.84	130	90	<5	2.24	1	34	28	254	8.11	<10	2.19	959	9	<0.01	9	1830	70	<5	<20	42	<0.01	<10	139	<10	<1	140
28	D96-174	155	3.2	2.99	105	135	<5	4.62	2	38	31	318	8.45	<10	1.99	1115	8	<0.01	13	2210	64	<5	<20	109	0.01	<10	162	<10	<1	145

QC/DATA:

Resplit:

1	D96-134	5	0.2	0.87	<5	1200	<5	3.51	4	3	26	46	3.72	<10	0.21	631	3	<0.01	3	1680	30	10	<20	84	0.03	<10	44	<10	<1	72
---	---------	---	-----	------	----	------	----	------	---	---	----	----	------	-----	------	-----	---	-------	---	------	----	----	-----	----	------	-----	----	-----	----	----

Repeat:

1	D96-134	5	0.4	0.90	<5	1260	<5	3.36	4	2	24	44	3.77	<10	0.21	613	3	<0.01	3	1690	30	<5	<20	84	0.03	<10	42	<10	<1	70
10	D96-143	130	0.6	3.48	5	200	10	7.87	2	22	10	30	6.73	<10	1.81	1550	4	<0.01	7	1540	8	<5	<20	130	0.02	<10	88	<10	<1	148
19	D96-152	110	0.4	4.26	35	195	10	5.95	3	23	17	37	8.55	<10	2.71	1271	7	<0.01	7	1400	24	<5	<20	216	0.02	<10	116	<10	<1	112

Standard:

GEO 96		140	1.4	1.84	65	175	<5	1.94	<1	20	66	84	4.01	<10	1.00	767	<1	0.02	22	790	24	<5	<20	66	0.12	<10	82	<10	3	67
--------	--	-----	-----	------	----	-----	----	------	----	----	----	----	------	-----	------	-----	----	------	----	-----	----	----	-----	----	------	-----	----	-----	---	----

df/5137
XLS/96Teuton#4

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AS 96-5145

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

15-Aug-96

ATTENTION: DINO CREMONESE

No. of samples received: 14
Sample Type: Rock
PROJECT #: Clone
SHIPMENT #: None given
P.O. #: None given
Samples submitted by: David Hick

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	As (%)	Cu (%)	Co (%)
3	D96-177	13.86	0.404	29.8	0.87	4.32	-	-
4	D96-178	21.92	0.639	40.5	1.18	4.13	-	-
5	D96-179	14.05	0.410	42.2	1.23	1.01	1.43	-
6	D96-180	22.06	0.643	-	-	-	-	-
7	D96-181	13.45	0.392	-	-	-	-	-
8	D96-182	6.02	0.178	-	-	-	-	-
9	D96-183	8.18	0.239	-	-	1.89	-	-
11	MM96-046	8.03	0.234	-	-	-	-	-
12	MM96-047	4.04	0.118	-	-	2.67	-	0.048

QC/DATA:

Standard:

CPB-1	-	-	629.0	18.34	-	0.25	-
CD-1	-	-	-	-	0.66	-	-
Sula	-	-	-	-	-	-	0.042

XLS96Teuton#4

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

14-Aug-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5145

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 14
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-28
P.O.#: NONE GIVEN
Samples submitted by: DAVID HICK


Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	D96-175	105	<0.2	0.93	220	65	<5	1.73	<1	16	64	128	4.49	<10	0.33	389	5	<0.01	3	1420	2	<5	<20	23	<0.01	<10	18	<10	<1	<1
2	D96-176	15	<0.2	2.43	35	155	<5	4.23	<1	12	92	27	4.65	<10	1.05	788	3	0.01	4	1300	4	<5	<20	68	0.01	<10	70	<10	<1	6
3	D96-177	>1000	>30	0.62	>10000	55	<5	7.26	<1	79	91	5691	>10	<10	0.32	1608	15	<0.01	22	170	6	<5	<20	78	<0.01	<10	16	<10	<1	34
4	D96-178	>1000	>30	0.19	>10000	50	<5	2.28	<1	41	97	9091	>10	<10	<0.01	486	13	<0.01	12	30	<2	<5	<20	19	<0.01	10	7	<10	<1	14
5	D96-179	>1000	>30	0.51	>10000	45	<5	3.35	<1	25	126	>10000	7.73	<10	0.20	659	8	<0.01	13	570	<2	<5	<20	36	0.01	<10	15	<10	<1	30
6	D96-180	>1000	19.6	0.14	1110	30	<5	0.04	<1	12	176	388	>10	<10	<0.01	35	10	<0.01	9	<10	4	<5	<20	<1	<0.01	30	6	<10	<1	<1
7	D96-181	>1000	22.0	0.56	7490	50	<5	2.16	<1	20	84	4851	>10	<10	0.33	501	14	<0.01	5	<10	2	<5	<20	30	<0.01	10	15	<10	<1	10
8	D96-182	>1000	6.0	1.05	6540	50	<5	>10	<1	19	68	1676	9.79	<10	0.70	1655	7	<0.01	11	380	<2	<5	<20	112	0.01	<10	27	<10	<1	13
9	D96-183	>1000	7.2	1.78	>10000	55	<5	3.00	<1	140	101	2742	>10	<10	1.41	882	14	<0.01	19	100	66	<5	<20	51	<0.01	<10	68	10	<1	94
10	D96-184	65	1.0	1.73	395	30	<5	2.26	<1	15	157	535	9.20	<10	1.44	618	7	<0.01	11	80	4	<5	<20	25	<0.01	<10	75	<10	<1	4
11	MM96-046	>1000	8.0	0.34	2625	50	<5	4.42	<1	38	81	1619	>10	<10	0.13	628	13	<0.01	32	10	12	<5	<20	85	<0.01	10	9	<10	<1	<1
12	MM96-047	>1000	15.4	1.47	>10000	45	<5	0.92	<1	449	96	3785	8.68	<10	1.07	630	6	<0.01	15	250	8	10	<20	16	<0.01	<10	56	20	<1	12
13	MM96-048	5	<0.2	2.96	40	45	<5	0.93	<1	30	23	131	6.85	<10	3.27	1348	<1	0.04	4	1920	2	<5	<20	27	0.20	<10	267	<10	5	65
14	MM96-049	5	<0.2	0.69	45	15	<5	0.72	<1	8	197	20	1.64	<10	0.68	360	<1	<0.01	9	200	<2	<5	<20	13	0.02	<10	54	<10	<1	3

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS-5145

ECO-TECH LABORATORIES LTD.



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5146

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2


15-Aug-96

ATTENTION: DINO CREMONESE

No. of samples received: 50
Sample Type: ROCK
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
P.O. #: NONE GIVEN
Samples submitted by: A. RAVEN

ET #.	Tag #	Au (g/t)	Au (oz/t)
14	ERK-96-64	25.88	0.755
15	ERK-96-65	15.34	0.447

XLS/96TEUTON#4

per 
ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

15-Aug-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AS-5146

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 50

Sample Type: ROCK

PROJECT #: NONE GIVEN

SHIPMENT #: NONE GIVEN

P.O.#: NONE GIVEN

Samples submitted by: A.RAVEN


Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	ERK-96-51	335	2.8	3.81	85	105	<5	3.91	4	48	25	812	>10	<10	3.27	1483	7	0.02	10	1080	44	<5	<20	106	<0.01	<10	173	<10	<1	214
2	ERK-96-52	5	0.4	3.30	15	70	<5	5.85	<1	46	20	215	7.52	<10	3.43	1145	11	0.02	6	1510	10	<5	<20	153	<0.01	<10	165	<10	<1	64
3	ERK-96-53	10	1.0	3.60	50	100	<5	5.69	12	38	20	293	7.65	<10	3.64	1298	7	0.02	8	1470	32	<5	<20	129	<0.01	<10	166	<10	<1	545
4	ERK-96-54	5	0.4	3.08	15	70	<5	4.77	<1	29	23	281	7.33	<10	3.07	1008	4	0.03	6	1570	10	<5	<20	104	<0.01	<10	184	<10	<1	48
5	ERK-96-55	10	0.2	3.30	45	110	<5	5.78	<1	46	19	395	9.68	<10	3.12	1013	10	0.04	8	1560	20	<5	<20	150	0.01	<10	197	<10	<1	41
6	ERK-96-56	40	<0.2	3.21	25	85	<5	3.30	1	40	25	362	9.30	<10	3.14	790	11	0.04	10	1790	18	<5	<20	96	<0.01	<10	213	<10	<1	36
7	ERK-96-57	255	4.0	3.38	80	90	<5	4.27	20	64	28	774	>10	<10	2.27	1740	16	<0.01	13	2410	106	<5	<20	66	0.01	<10	184	<10	<1	675
8	ERK-96-58	15	1.6	4.96	60	120	<5	2.39	5	29	25	260	>10	<10	3.02	3420	15	<0.01	12	2320	92	<5	<20	43	0.01	<10	223	<10	<1	444
9	ERK-96-59	5	1.2	3.51	30	165	<5	7.37	23	18	29	153	7.60	<10	2.84	3214	7	<0.01	11	2040	252	<5	<20	134	0.01	<10	145	<10	<1	948
10	ERK-96-60	40	2.8	4.05	180	90	<5	5.58	<1	39	26	415	>10	<10	3.82	1526	12	0.02	10	2130	22	<5	<20	159	0.02	<10	279	<10	<1	73
11	ERK-96-61	70	3.8	4.84	210	75	<5	4.06	<1	32	27	459	>10	<10	4.58	2343	34	0.01	11	1990	28	<5	<20	100	0.02	<10	291	<10	<1	87
12	ERK-96-62	100	3.6	3.68	135	95	<5	5.28	<1	25	40	295	>10	<10	3.10	1701	8	0.02	13	2090	16	<5	<20	118	0.02	<10	274	<10	<1	60
13	ERK-96-63	15	2.0	4.53	105	85	<5	5.29	<1	26	34	247	>10	<10	4.33	1828	12	0.02	12	2220	24	<5	<20	98	0.02	<10	288	<10	<1	90
14	ERK-96-64	>1000	18.6	4.46	210	70	<5	1.67	<1	65	14	836	>10	<10	3.62	1968	247	0.01	26	2110	62	<5	<20	25	0.01	<10	272	<10	<1	103
15	ERK-96-65	>1000	5.2	3.80	85	120	<5	3.15	<1	31	13	212	>10	<10	2.84	1866	100	0.02	15	2790	20	<5	<20	88	0.02	<10	323	<10	<1	77
16	ERK-96-66	190	0.4	3.66	50	110	<5	4.24	<1	21	19	147	9.67	<10	2.95	1640	11	0.03	9	2480	16	<5	<20	83	0.02	<10	361	<10	<1	75
17	ERK-96-67	45	0.4	3.34	30	120	5	2.31	<1	18	18	104	8.70	<10	2.78	1140	7	0.04	13	2560	18	<5	<20	53	0.02	<10	356	<10	<1	59
18	ERK-96-68	5	<0.2	3.62	60	105	5	3.33	<1	36	12	33	9.55	<10	2.75	1391	6	0.04	7	2530	12	<5	<20	69	0.03	<10	330	<10	<1	56
19	ERK-96-69	25	1.6	2.51	15	260	<5	3.46	1	21	16	46	5.21	<10	1.36	1334	4	<0.01	3	1360	26	<5	<20	54	0.01	<10	39	<10	2	224
20	ERK-96-70	5	1.4	3.68	20	275	10	7.90	5	24	9	56	8.25	<10	2.28	3092	6	<0.01	6	1690	72	<5	<20	143	0.02	<10	97	<10	<1	347
21	ERK-96-71	10	0.6	2.82	<5	445	5	5.47	4	18	17	17	5.43	<10	1.27	2133	4	<0.01	7	1910	38	<5	<20	112	0.01	<10	68	<10	3	257
22	ERK-96-72	105	2.4	3.20	50	225	<5	3.14	3	31	13	47	7.64	<10	1.79	1858	6	<0.01	9	2110	110	10	<20	54	<0.01	<10	75	<10	<1	467
23	ERK-96-73	5	9.8	3.56	55	190	<5	0.65	3	50	17	1425	9.52	<10	1.91	828	17	<0.01	13	2010	76	<5	<20	11	<0.01	<10	103	<10	<1	575
24	ERK-96-74	10	5.6	3.01	110	220	<5	3.03	43	47	17	230	7.91	<10	1.50	1649	8	0.01	10	1930	248	<5	<20	41	0.01	<10	80	<10	<1	1977
25	ERK-96-75	60	1.8	2.30	105	140	<5	7.30	3	24	26	34	6.41	<10	1.36	2830	8	<0.01	6	1520	78	<5	<20	105	<0.01	<10	63	<10	1	272

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	ERK-96-76	5	0.2	2.27	10	275	5	1.83	<1	16	26	9	4.94	<10	0.77	779	4	<0.01	2	1440	18	<5	<20	44	0.01	<10	35	<10	<1	87
27	ERK-96-77	5	3.8	2.86	45	200	<5	6.50	18	28	19	101	6.43	<10	1.46	2278	9	<0.01	9	1590	150	<5	<20	110	0.01	<10	65	<10	<1	859
28	ERK-96-78	5	0.8	3.09	<5	325	5	9.96	5	18	13	16	6.30	<10	1.57	3487	4	<0.01	5	1390	24	<5	<20	161	0.02	<10	62	<10	1	365
29	ERK-96-79	260	1.0	2.82	15	310	10	7.61	6	23	13	19	5.08	<10	1.67	2925	4	<0.01	5	1750	46	5	<20	122	0.01	<10	53	<10	4	395
30	ERK-96-80	5	1.4	2.91	35	250	<5	6.18	2	18	12	83	5.86	<10	1.43	2636	6	<0.01	10	2000	46	<5	<20	83	0.01	<10	80	<10	<1	242
31	ERK-96-81	5	3.4	3.21	55	165	<5	3.74	6	32	20	177	8.94	<10	1.39	2276	8	<0.01	11	2040	84	<5	<20	48	0.01	<10	89	<10	<1	415
32	ERK-96-82	5	5.6	2.98	95	190	<5	5.44	1	46	23	693	7.21	<10	1.34	2229	8	<0.01	16	1830	150	<5	<20	85	0.01	<10	88	<10	<1	285
33	ERK-96-83	10	4.4	3.40	30	265	<5	5.38	2	27	18	99	7.40	<10	2.12	2215	7	<0.01	8	1900	72	<5	<20	92	0.01	<10	90	<10	<1	224
34	ERK-96-84	45	2.2	3.57	5	270	10	5.18	3	18	24	23	8.62	<10	1.82	2322	6	<0.01	5	1690	32	<5	<20	81	0.01	<10	104	<10	<1	197
35	ERK-96-85	5	0.6	2.92	5	385	10	5.46	4	18	16	11	5.97	<10	1.42	2258	4	<0.01	6	1770	28	<5	<20	112	0.01	<10	87	<10	<1	296
36	ERK-96-86	50	0.8	3.40	25	310	10	8.68	11	29	16	13	8.42	<10	2.07	4004	7	<0.01	6	1620	52	<5	<20	207	0.02	<10	105	<10	2	398
37	ERK-96-87	20	0.6	3.13	20	245	5	6.64	3	22	21	16	6.29	<10	2.19	2695	4	<0.01	7	1430	34	<5	<20	126	0.01	<10	79	<10	<1	268
38	ERK-96-88	5	2.6	3.49	50	185	<5	7.11	3	32	20	461	8.54	<10	2.36	2119	8	0.01	14	1770	72	<5	<20	110	<0.01	<10	105	<10	<1	273
39	ERK-96-89	5	1.4	3.20	35	245	<5	7.17	3	22	21	71	6.72	<10	1.61	2487	7	<0.01	10	1970	64	<5	<20	104	0.01	<10	69	<10	2	178
40	ERK-96-90	5	<0.2	2.40	10	825	5	4.81	<1	14	11	14	5.29	<10	1.32	1397	3	<0.01	8	1400	12	<5	<20	126	0.01	<10	36	<10	2	69
41	ERK-96-91	5	0.8	2.99	5	750	<5	4.20	<1	20	17	233	5.91	<10	1.53	1512	4	<0.01	7	1330	14	<5	<20	115	0.02	<10	49	<10	<1	124
42	ERK-96-92	5	1.0	2.95	<5	315	10	5.03	1	21	31	29	>10	<10	1.45	1768	7	<0.01	6	1240	28	<5	<20	122	0.03	<10	140	<10	<1	167
43	ERK-96-93	365	17.0	4.07	20	205	10	7.75	2	30	22	24	9.16	<10	2.86	2838	7	<0.01	8	1600	36	<5	<20	118	0.01	<10	126	<10	<1	230
44	ERK-96-94	5	0.6	3.07	35	160	10	4.34	2	21	13	14	6.70	<10	2.13	2149	4	<0.01	4	1780	36	<5	<20	89	<0.01	<10	53	<10	<1	320
45	ERK-96-95	165	1.4	2.64	55	285	5	4.27	6	16	18	26	7.17	<10	1.59	3146	7	<0.01	3	1450	100	<5	<20	93	<0.01	<10	59	<10	<1	348
46	ERK-96-96	5	0.2	3.66	<5	335	10	9.22	11	22	22	12	8.03	<10	2.00	3430	6	<0.01	8	1940	30	<5	<20	181	0.02	<10	102	<10	<1	363
47	ERK-96-97	5	0.2	3.29	10	300	10	8.36	2	24	23	13	7.97	<10	1.98	2620	6	<0.01	10	1940	34	<5	<20	127	0.01	<10	105	<10	<1	296
48	ERK-96-98	5	2.4	3.48	70	185	<5	>10	3	26	28	255	8.05	<10	2.26	3056	8	0.01	10	1520	76	<5	<20	164	0.01	<10	108	<10	<1	271
49	ERK-96-99	5	3.8	3.61	75	140	<5	>10	1	31	29	514	9.04	<10	2.43	2819	8	0.01	12	1620	100	<5	<20	166	0.01	<10	127	<10	<1	242
50	ERK-96-100	5	2.6	3.32	110	155	<5	>10	1	25	33	168	7.52	<10	2.20	3109	10	0.02	16	1600	134	<5	<20	203	0.01	<10	100	<10	<1	219

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
QC/DATA:																															
Resplit:																															
1	ERK-96-51	350	2.8	3.90	110	100	<5	4.18	4	49	30	692	>10	<10	3.31	1568	8	0.01	10	1380	64	<5	<20	104	<0.01	<10	179	<10	<1	279	
36	ERK-96-86	50	0.8	3.43	25	330	10	9.01	11	30	13	11	8.86	<10	2.07	4130	8	<0.01	9	1770	64	<5	<20	215	0.02	<10	109	<10	2	441	
Repeat:																															
1	ERK-96-51	340	2.6	3.84	100	90	<5	4.22	4	54	27	787	>10	<10	3.29	1573	8	0.01	12	1230	58	<5	<20	106	<0.01	<10	177	<10	<1	260	
10	ERK-96-80	40	2.8	3.96	190	90	<5	5.56	<1	38	26	404	>10	<10	3.77	1512	12	0.02	13	2180	24	<5	<20	155	0.02	<10	275	<10	<1	73	
19	ERK-96-69	15	1.6	2.48	15	225	<5	3.54	2	23	17	48	5.42	<10	1.37	1361	4	<0.01	4	1440	32	<5	<20	54	<0.01	<10	38	<10	1	238	
36	ERK-96-86	60	0.8	3.32	25	240	10	8.75	10	29	16	13	8.54	<10	2.06	4038	7	<0.01	8	1640	54	<5	<20	215	0.02	<10	104	<10	2	410	
45	ERK-96-95	160	1.2	2.70	70	290	10	4.37	7	17	20	26	7.40	<10	1.59	3211	8	<0.01	4	1550	110	<5	<20	95	0.01	<10	61	<10	<1	374	
Standard:																															
GEO 96		150	1.4	1.82	60	170	<5	2.04	<1	22	70	83	4.04	<10	1.00	720	<1	0.02	24	710	20	<5	<20	70	0.13	<10	83	<10	4	77	
GEO 96		150	1.2	1.91	65	180	<5	1.92	<1	23	73	85	4.01	<10	1.02	720	<1	0.02	31	710	20	<5	<20	64	0.13	<10	86	<10	4	80	

df/5146
XLS/96Teuton#4


ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5147

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

18-Sep-96

ATTENTION: DINO CREMONESE

No. of samples received: 22
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-30
P.O.#: NONE GIVEN
Samples submitted by: DAVID HICK

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	As (%)	Co (%)
1	D96-185	23.22	0.677	-	-	-	-
2	D96-186	4.94	0.144	35.6	1.04	6.65	0.199
3	D96-187	6.16	0.180	-	-	-	-
4	D96-188	14.57	0.425	-	-	-	-
5	D96-189	4.61	0.134	-	-	-	-
6	D96-190	26.36	0.769	-	-	-	-
7	D96-191	8.44	0.246	-	-	-	-
8	D96-192	5.51	0.161	-	-	3.17	-
9	D96-193	2.77	0.081	-	-	-	-
14	MM96-054	1.63	0.048	83.1	2.42	-	-


QC/DATA:

Resplit:

R/S 1	D96-185	24.31	0.709	-	-	-	-
-------	---------	-------	-------	---	---	---	---

Standard:

CPB-1	-	-	629.0	18.34	-	-
CD-1	-	-	-	-	0.66	-
Su1a	-	-	-	-	-	0.042


ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

XLS/96Teuton#8

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AS-5147

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 22
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S98-30
P.O.#: NONE GIVEN
Samples submitted by: DAVID HICK

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	BI	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	TI %	U	V	W	Y	Zn
1	D96-185	>1000	25.6	0.72	4380	45	<5	0.07	<1	106	72	1034	>10	<10	0.50	167	13	<0.01	19	<10	58	<5	<20	3	<0.01	10	28	10	<1	22
2	D96-186	>1000	>30	1.23	>10000	55	<5	1.27	<1	1485	74	7714	>10	<10	1.03	507	18	<0.01	30	<10	32	<5	<20	20	<0.01	10	58	10	<1	35
3	D96-187	>1000	14.6	3.01	4680	70	<5	5.91	<1	59	100	4562	>10	<10	2.00	1243	17	<0.01	39	570	4	<5	<20	106	<0.01	<10	102	<10	<1	28
4	D96-188	>1000	14.2	2.09	4345	65	<5	3.66	<1	41	66	1505	>10	<10	1.35	823	14	<0.01	22	190	28	<5	<20	50	<0.01	10	64	<10	<1	16
5	D96-189	>1000	2.6	0.68	1590	45	<5	1.98	<1	83	70	359	>10	<10	0.36	449	14	<0.01	33	230	12	<5	<20	32	<0.01	10	29	<10	<1	2
6	D96-190	>1000	19.0	0.72	1730	50	<5	2.07	<1	39	64	5496	>10	<10	0.49	370	16	<0.01	21	<10	90	<5	<20	33	<0.01	10	23	<10	<1	19
7	D96-191	>1000	4.8	1.48	480	65	<5	2.28	<1	30	56	520	>10	<10	0.63	1118	13	<0.01	30	790	32	<5	<20	38	<0.01	<10	49	<10	<1	74
8	D96-192	>1000	4.4	1.08	>10000	55	<5	2.21	<1	114	65	937	>10	<10	0.55	873	15	<0.01	27	250	22	<5	<20	37	<0.01	<10	26	<10	<1	53
9	D96-193	>1000	6.0	2.39	4120	60	<5	0.37	<1	22	66	655	>10	<10	1.15	501	9	<0.01	5	950	<2	<5	<20	8	<0.01	10	66	<10	<1	18
10	MM96-050	50	<0.2	2.50	55	80	<5	1.55	<1	16	77	132	3.99	<10	1.59	430	3	0.07	12	1580	<2	<5	<20	54	0.09	<10	141	<10	3	14
11	MM96-051	150	0.8	0.29	120	35	20	0.08	<1	77	88	49	>10	<10	0.12	99	94	<0.01	17	210	<2	<5	<20	2	0.01	10	12	<10	<1	<1
12	MM96-052	20	0.8	2.61	20	20	<5	>10	<1	7	17	25	5.17	<10	2.12	4122	4	<0.01	2	180	<2	<5	<20	504	0.01	<10	33	<10	14	6
13	MM96-053	25	<0.2	2.27	20	45	<5	2.90	<1	16	68	133	2.54	<10	0.87	399	6	0.03	23	1860	2	<5	<20	30	0.09	<10	98	<10	4	20
14	MM96-054	>1000	>30	0.67	705	30	<5	0.24	<1	38	121	463	9.67	<10	0.44	461	26	<0.01	20	750	4	160	<20	4	<0.01	<10	25	<10	<1	31
15	MM96-055	560	0.6	0.84	585	40	10	0.17	<1	36	137	108	>10	<10	0.52	383	11	<0.01	15	430	<2	<5	<20	2	0.04	<10	43	<10	<1	<1
16	MM96-056	325	0.6	0.65	255	30	5	0.19	<1	47	129	58	8.25	<10	0.36	189	28	<0.01	13	920	<2	<5	<20	2	<0.01	10	28	<10	<1	<1
17	MM96-057	90	0.8	0.72	60	30	5	0.22	<1	36	112	18	5.59	<10	0.29	365	42	<0.01	10	650	<2	<5	<20	3	<0.01	<10	18	<10	<1	<1
18	MM96-058	305	0.4	0.52	320	35	<5	0.07	<1	25	125	5	5.35	<10	0.12	109	12	<0.01	6	570	<2	<5	<20	1	<0.01	10	14	<10	<1	<1
19	MM96-059	205	0.6	0.46	240	30	15	0.05	<1	57	117	31	8.28	<10	0.14	92	112	<0.01	9	390	6	<5	<20	1	<0.01	10	15	<10	<1	<1
20	MM96-060	25	1.4	1.91	<5	25	<5	1.61	<1	21	47	568	6.73	<10	0.59	1003	9	0.07	6	1500	<2	<5	<20	47	0.05	<10	70	10	<1	22
21	MM96-061	5	0.2	0.16	25	30	5	<0.01	<1	40	113	15	4.61	<10	<0.01	42	7	<0.01	8	260	<2	<5	<20	2	<0.01	10	7	<10	<1	<1
22	MM96-062	275	4.2	0.88	115	50	<5	0.08	<1	14	126	680	5.94	<10	0.39	375	19	<0.01	5	440	4	<5	<20	2	0.01	<10	28	<10	<1	<1

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC/DATA:																														
<i>Repeat:</i>																														
1	D96-185	>1000	26.4	0.81	4355	45	<5	0.08	<1	100	84	1114	>10	<10	0.60	177	14	<0.01	17	<10	54	<5	<20	1	<0.01	10	32	10	<1	23
<i>Repeat:</i>																														
1	D96-185	>1000	26.4	0.70	4350	45	<5	0.07	<1	102	68	1079	>10	<10	0.52	152	12	<0.01	17	<10	52	<5	<20	2	<0.01	10	28	10	<1	20
10	MM96-050	55	<0.2	2.53	50	80	<5	1.62	<1	16	79	132	4.09	<10	1.60	443	2	0.07	13	1640	<2	<5	<20	54	0.10	<10	144	<10	3	16
19	MM96-059	230	0.6	0.46	250	30	15	0.05	<1	57	119	32	8.35	<10	0.14	95	113	<0.01	9	400	6	<5	<20	<1	<0.01	10	14	<10	<1	<1
<i>Standard:</i>																														
GEO 96		145	1.4	1.81	60	150	<5	1.84	<1	18	60	88	4.03	<10	1.01	698	<1	0.02	23	670	18	<5	<20	59	0.11	<10	79	<10	3	72

dl/5137
XLS/96Teuton#4


 ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5158

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2


16-Aug-96

ATTENTION: DINO CREMONESE

No. of samples received: 7
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-31
P.O. #: NONE GIVEN
Samples submitted by: R. MCLEOD

ET #.	Tag #	Au (g/t)	Au (oz/t)
5	RJM96-033	1.27	0.037

XLS/96Teuton#4


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5158

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 7
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-31
P.O. #: NONE GIVEN
Samples submitted by: R.MCLEOD

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	RJM96-026	5	0.8	1.86	55	350	<5	9.55	<1	31	72	100	6.32	<10	1.22	1749	7	0.05	35	1850	12	5	<20	171	0.03	<10	87	<10	5	72
2	RJM96-027	45	1.8	2.36	50	320	<5	5.65	<1	26	91	285	5.92	<10	1.55	1161	8	0.01	28	1450	8	40	<20	102	0.04	<10	84	<10	3	37
3	RJM96-030	65	0.8	1.54	40	115	<5	0.63	<1	14	181	62	3.55	<10	1.02	416	6	0.02	20	590	8	<5	<20	17	0.01	<10	59	<10	<1	25
4	RJM96-031	5	<0.2	0.19	<5	45	<5	1.93	<1	3	197	9	1.13	<10	0.18	343	3	<0.01	4	160	<2	<5	<20	47	<0.01	<10	5	<10	<1	16
5	RJM96-033	>1000	2.2	0.39	180	65	<5	0.04	<1	24	195	224	2.80	<10	0.19	147	15	<0.01	11	90	6	<5	<20	<1	<0.01	<10	9	<10	1	12
6	RJM96-034	25	11.0	0.50	40	50	<5	0.07	<1	17	150	2943	5.61	<10	0.19	110	19	<0.01	8	500	<2	<5	<20	1	<0.01	<10	21	<10	<1	7
7	RJM96-035	5	0.4	0.33	5	35	<5	6.05	<1	4	146	19	1.25	<10	0.19	1160	7	<0.01	14	390	6	<5	<20	256	<0.01	<10	14	<10	3	48

QC/DATA:**Resplit:**

1	RJM96-026	5	1.0	1.78	60	310	<5	9.49	<1	30	67	100	6.25	<10	1.20	1724	6	0.04	33	1860	12	10	<20	166	0.02	<10	80	<10	4	71
---	-----------	---	-----	------	----	-----	----	------	----	----	----	-----	------	-----	------	------	---	------	----	------	----	----	-----	-----	------	-----	----	-----	---	----

Repeat:

1	RJM96-026	5	1.0	1.77	55	335	<5	9.65	<1	31	69	98	6.38	<10	1.23	1771	7	0.05	35	1900	14	10	<20	173	0.02	<10	83	<10	4	72
---	-----------	---	-----	------	----	-----	----	------	----	----	----	----	------	-----	------	------	---	------	----	------	----	----	-----	-----	------	-----	----	-----	---	----

Standard:

GEO'96		150	1.2	1.92	65	155	5	1.85	<1	19	66	79	4.18	<10	1.01	709	<1	0.03	25	720	18	<5	<20	68	0.14	<10	85	<10	5	64
--------	--	-----	-----	------	----	-----	---	------	----	----	----	----	------	-----	------	-----	----	------	----	-----	----	----	-----	----	------	-----	----	-----	---	----

dl/5157R
XLS/96Teuton#4


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AS 96-5162

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

21-Aug-96

ATTENTION: DINO CREMONESE

No. of samples received: 18
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-32
P. O. #: NONE GIVEN
Samples submitted by: DAVID HICK

ET #.	Tag #	Au (g/t)	Au (oz/t)	As (%)	Co (%)
1	D-96-194	1.32	0.038	-	-
3	D-96-196	2.29	0.067	6.55	0.041

QC/DATA:

Resplit:

R/S 1	D-96-194	1.43	0.042	-	-
-------	----------	------	-------	---	---

Standard:

Sula	-	-	-	0.041
Cd-1	-	-	0.66	-

XLS/96TEUTON#5

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

19-Aug-98

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5162

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 18
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-32
P.O.#: NONE GIVEN
Samples submitted by: DAVID HICK

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	D-96-184	>1000	3.0	1.27	8105	70	<5	0.16	<1	95	41	1429	>10	<10	1.00	263	17	0.03	33	<10	6	<5	<20	6	0.02	<10	38	<10	<1	26
2	D-96-185	770	1.2	2.29	1400	70	<5	0.49	<1	33	37	1032	>10	<10	2.09	431	8	0.13	16	1220	8	<5	<20	25	0.11	<10	135	<10	<1	29
3	D-96-186	>1000	1.8	1.38	>10000	60	<5	0.28	<1	371	55	473	>10	<10	1.23	365	13	0.04	18	440	6	100	<20	11	0.02	<10	73	<10	<1	20
4	D-96-187	15	7.8	0.48	115	40	<5	>10	<1	12	58	3018	6.57	<10	0.67	4672	10	<0.01	11	340	<2	<5	<20	136	0.01	<10	30	<10	<1	11
5	D-96-188	30	0.2	2.23	80	70	<5	1.66	<1	55	43	811	7.66	<10	1.56	605	1	0.11	20	2580	22	<5	<20	34	0.26	<10	325	<10	1	39
6	D-96-199	5	3.4	1.16	260	65	<5	>10	101	35	53	483	6.70	<10	3.37	2496	2	0.02	18	1110	28	<5	<20	304	0.01	<10	68	<10	<1	5942
7	D-96-200	10	1.6	1.46	30	80	<5	7.35	6	14	54	204	6.07	<10	2.73	1553	4	0.04	17	1490	30	<5	<20	245	<0.01	<10	67	<10	6	449
8	D-96-201	10	4.6	1.81	55	80	<5	8.59	6	17	42	999	7.78	<10	3.38	1376	5	0.04	16	1320	162	<5	<20	364	0.02	<10	77	<10	4	519
9	D-96-202	5	5.2	1.53	100	75	<5	8.30	5	25	49	958	8.04	<10	3.02	1595	6	0.04	22	1180	74	<5	<20	314	0.01	<10	71	<10	<1	419
10	D-96-203	80	7.4	1.71	335	75	<5	2.82	<1	172	36	373	>10	<10	1.23	1216	16	<0.01	33	900	86	<5	<20	73	<0.01	<10	55	<10	<1	19
11	D-96-204	65	2.8	2.22	265	100	20	1.38	<1	58	22	59	>10	<10	1.31	833	17	<0.01	34	930	58	<5	<20	45	0.02	<10	54	<10	<1	29
12	D-96-205	10	1.4	1.90	95	55	<5	>10	<1	31	68	65	7.36	<10	3.00	2493	6	0.04	21	1010	12	<5	<20	327	0.02	<10	80	<10	3	112
13	D-96-206	15	1.0	1.41	15	65	5	>10	4	12	24	22	6.27	<10	3.41	2694	4	0.02	5	810	4	<5	<20	281	0.02	<10	40	<10	3	230
14	D-96-207	90	1.0	0.87	470	60	15	4.73	<1	24	63	43	>10	<10	0.92	741	14	<0.01	5	<10	8	<5	<20	74	0.01	<10	67	<10	<1	16
15	D-96-208	35	0.6	1.01	365	80	20	7.02	<1	36	79	21	>10	<10	0.92	1444	12	<0.01	9	<10	4	<5	<20	111	0.02	<10	52	<10	<1	17
16	D-96-209	95	0.2	1.24	425	55	30	4.80	<1	25	81	67	>10	<10	1.24	825	17	<0.01	10	200	22	<5	<20	69	<0.01	<10	61	<10	<1	20
17	D-96-210	80	0.4	1.57	590	65	20	7.31	<1	38	63	52	>10	<10	1.63	1574	13	<0.01	16	100	6	<5	<20	154	0.02	<10	78	<10	<1	22
18	MM96-063	525	1.2	1.05	295	65	15	0.26	<1	28	59	26	7.47	<10	0.35	291	16	<0.01	12	1140	12	<5	<20	3	<0.01	<10	32	<10	<1	13

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS-5162

ECO-TECH LABORATORIES LTD.

22-Aug-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5176

TEUTON RESOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 18
Sample Type: Rock
PROJECT #: Clone
SHIPMENT #: S96-33
P.O.#: None Given
Samples submitted by: David Hick

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	D96-211	5	<0.2	0.56	30	215	10	1.31	<1	7	66	5	3.15	<10	0.16	329	<1	<0.01	2	1350	12	45	<20	18	0.14	<10	48	<10	4	24
2	D96-212	5	<0.2	0.52	<5	250	<5	5.44	<1	<1	132	6	0.73	<10	0.01	665	3	<0.01	2	280	2	10	<20	182	0.05	<10	19	<10	<1	<1
3	D96-213	5	<0.2	0.45	<5	245	<5	7.83	<1	3	142	<1	0.71	<10	0.40	1492	<1	<0.01	4	120	<2	10	<20	93	<0.01	<10	6	<10	<1	17
4	D96-214	10	0.4	1.78	175	100	10	0.38	<1	19	31	5	4.71	<10	1.07	709	4	0.02	1	1670	14	<5	<20	12	<0.01	<10	66	<10	1	93
5	D96-215	5	<0.2	2.88	<5	165	15	1.23	<1	36	25	10	6.97	<10	3.56	1821	<1	0.03	11	930	8	<5	<20	26	0.37	<10	226	<10	4	77
6	D96-216	5	<0.2	2.79	<5	205	15	1.50	<1	30	21	11	6.68	<10	3.08	1089	<1	0.02	9	1100	8	<5	<20	35	0.25	<10	136	<10	2	60
7	D96-217	10	<0.2	4.83	30	115	<5	1.82	2	30	26	132	8.24	<10	2.36	720	<1	0.30	10	2020	38	<5	<20	137	0.20	<10	241	<10	<1	278
8	D96-218	5	<0.2	0.80	<5	30	<5	0.12	<1	4	196	12	1.82	<10	0.50	201	7	<0.01	18	180	4	<5	<20	10	<0.01	<10	19	<10	<1	69
9	D96-219	10	0.4	0.90	40	310	5	0.27	<1	12	14	<1	5.70	<10	0.07	835	8	<0.01	4	1240	18	<5	<20	17	<0.01	<10	16	<10	4	55
10	D96-220	5	<0.2	1.68	<5	210	10	0.67	<1	18	24	<1	4.75	<10	1.15	534	<1	0.02	2	1020	16	<5	<20	45	0.21	<10	35	<10	3	113
11	D96-221	5	<0.2	1.68	<5	250	15	0.67	<1	18	25	<1	>10	<10	0.72	637	6	0.02	4	620	12	<5	<20	8	0.07	<10	69	<10	<1	54
12	D96-222	255	2.4	1.17	450	65	<5	6.77	<1	31	78	52	6.97	<10	1.84	1169	5	<0.01	13	1700	4	<5	<20	180	<0.01	<10	81	<10	3	43
13	D96-223	110	3.0	0.17	130	40	<5	>10	<1	7	60	27	3.83	<10	2.25	1383	2	<0.01	12	310	2	10	<20	534	<0.01	<10	17	<10	<1	22
14	D96-224	70	2.8	0.91	140	40	5	0.41	<1	15	65	62	6.04	<10	0.54	176	27	<0.01	51	1020	18	<5	<20	24	<0.01	10	26	<10	<1	44
15	D96-225	10	1.0	1.16	<5	70	<5	0.42	3	12	14	58	5.72	<10	0.71	369	7	0.04	3	2180	70	<5	<20	18	0.15	<10	113	<10	<1	177
16	D96-226	5	<0.2	1.76	<5	65	<5	0.73	2	37	18	169	6.07	<10	1.30	621	3	0.06	9	2540	50	<5	<20	25	0.15	<10	161	<10	3	69
17	D96-227	5	<0.2	0.51	<5	40	<5	0.18	<1	15	16	34	5.44	<10	0.12	52	4	0.04	5	1340	14	<5	<20	9	0.04	<10	74	<10	<1	3
18	D96-228	65	0.4	0.14	25	20	10	0.01	<1	32	91	12	5.80	<10	<0.01	16	8	<0.01	12	20	2	<5	<20	2	<0.01	10	6	<10	<1	<1

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS-5176

ECO-TECH LABORATORIES LTD.

CERTIFICATE OF ASSAY AS 96-5177

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

23-Aug-96

ATTENTION: DINO CREMONESE

No. of samples received: 12
Sample Type: Core
PROJECT #: Clone
SHIPMENT #: S96-34
P.O.#: None Given
Samples submitted by: Milo Woodward

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Co (%)
1	ERK-96-101	-	-	29.3	0.85	1.25	-
3	ERK-96-103	16.38	0.477	-	-	-	0.057
7	ERK-96-107	16.67	0.486	-	-	-	0.062
8	ERK-96-108	3.06	0.089	-	-	-	-
11	ERK-96-111	4.79	0.140	-	-	-	0.064
12	ERK-96-112	2.41	0.070	-	-	-	0.033

QC DATA:

Resplit:

1	ERK-96-101	-	-	28.9	0.84	1.21	-
---	------------	---	---	------	------	------	---

Standard:

CPb-I	-	-	631.0	18.40	0.25	-	-
SUI-a	-	-	-	-	-	-	0.041

XLS/96Teuton#5

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

22-Aug-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 8T4

ICP CERTIFICATE OF ANALYSIS - AS-5177

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 12
Sample Type: Core
PROJECT #: Clone
SHIPMENT #: S96-34
P.O.#: None Given
Samples submitted by: Milo Woodward

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn	
1	ERK-96-101	170	>30	1.65	95	495	<5	0.99	10	11	12	>10000	8.88	<10	0.78	475	4	<0.01	2	1720	26	25	<20	30	0.09	<10	101	<10	<1	62	
2	ERK-96-102	100	<0.2	1.75	50	105	<5	3.91	<1	17	43	109	3.54	<10	1.08	773	4	0.04	8	1540	18	<5	<20	70	0.01	<10	104	<10	<1	66	
3	ERK-96-103	>1000	3.6	2.85	9625	120	<5	2.97	<1	570	20	451	9.13	<10	1.44	963	32	0.02	10	1390	30	<5	<20	56	0.02	<10	119	<10	<1	120	
4	ERK-96-104	20	<0.2	2.18	365	95	<5	4.24	<1	29	40	38	4.14	<10	1.61	909	3	0.05	7	1580	12	<5	<20	101	0.03	<10	119	<10	<1	45	
5	ERK-96-105	760	0.4	2.42	1235	155	<5	1.81	<1	52	19	107	5.36	<10	1.39	894	8	0.04	5	1120	26	<5	<20	51	0.02	<10	75	<10	<1	102	
6	ERK-96-106	80	<0.2	2.04	135	140	<5	4.14	<1	40	30	67	4.22	<10	1.16	891	3	0.03	6	1480	12	<5	<20	103	0.02	<10	88	<10	<1	60	
7	ERK-96-107	>1000	3.0	2.80	8430	115	<5	3.78	<1	640	11	287	8.52	<10	1.47	1146	23	0.03	11	1200	36	<5	<20	78	0.02	<10	116	<10	<1	158	
8	ERK-96-108	>1000	0.4	2.26	3915	95	5	4.60	<1	44	22	45	4.88	<10	1.60	991	8	0.04	4	1100	18	<5	<20	99	0.01	<10	78	<10	<1	56	
9	ERK-96-109	210	<0.2	2.62	125	95	<5	4.93	<1	22	23	71	5.32	<10	1.81	1105	4	0.03	3	1070	16	<5	<20	175	0.01	<10	70	<10	1	50	
10	ERK-96-110	115	<0.2	2.37	440	120	<5	2.68	<1	57	41	96	4.89	<10	1.69	814	1	0.07	7	1780	16	<5	<20	86	0.08	<10	175	<10	1	59	
11	ERK-96-111	>1000	3.4	2.78	7515	115	<5	3.39	<1	673	26	546	9.12	<10	1.23	922	8	0.02	9	1570	20	<5	<20	71	0.04	<10	115	<10	<1	102	
12	ERK-96-112	>1000	0.4	2.87	4995	140	<5	5.60	<1	313	17	92	5.70	<10	1.35	1129	8	0.02	5	1120	18	<5	<20	111	0.05	<10	82	<10	2	105	
QC/DATA:																															
<i>Resplit:</i>																															
R/S 1	ERK-96-101	190	>30	1.82	95	510	<5	0.96	10	11	15	>10000	9.40	<10	0.78	489	4	0.01	3	1880	30	20	<20	31	0.09	<10	110	<10	<1	62	
<i>Repeat:</i>																															
1	ERK-96-101	70	>30	1.67	100	505	<5	1.02	10	11	12	>10000	9.08	<10	0.78	483	4	<0.01	2	1870	26	15	<20	30	0.10	<10	103	<10	<1	62	
6	ERK-96-106	90	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
<i>Standard:</i>																															
GEO96		150	1.4	1.94	65	165	<5	1.92	<1	20	69	83	4.28	<10	1.00	737	<1	0.02	25	790	26	<5	<20	60	0.14	<10	86	<10	3	68	

dl/5176r
XLS/96Teuton#5

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AS 96-5181

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

26-Aug-96

ATTENTION: DINO CREMONESE

No. of samples received: 19
Sample Type: CORE
PROJECT #: CLONE
SHIPMENT #: C96-35
P.O.#: NONE GIVEN
Samples submitted by: MILO WOODWARD

ET #.	Tag #	Au (g/t)	Au (oz/t)	Co (%)
3	ERK-96-115	1.69	0.049	-
6	ERK-96-118	14.43	0.421	-
8	ERK-96-120	8.87	0.259	0.048

QC/DATA:

Standard:

SU-1a - - 0.041

XLS/96Teuton#5

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

26-Aug-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5181

TEUTON RESOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V8C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 19
Sample Type: CORE
PROJECT #: CLONE
SHIPMENT #: C96-35
P.O.#: NONE GIVEN
Samples submitted by: MILO WOODWARD

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Bn	Sr	Ti %	U	V	W	Y	Zn
1	ERK-96-113	30	<0.2	2.90	105	210	<5	2.71	<1	21	30	54	5.00	<10	1.84	884	3	0.14	3	1010	6	5	<20	90	0.11	<10	84	<10	4	51
2	ERK-96-114	35	<0.2	2.44	105	150	<5	4.91	<1	18	21	44	4.19	<10	1.18	900	2	0.10	4	1010	4	5	<20	148	0.07	<10	85	<10	4	45
3	ERK-96-115	>1000	0.6	3.10	1455	250	<5	3.59	<1	148	42	133	6.47	<10	1.72	1037	7	0.10	9	1550	2	<5	<20	108	0.04	20	147	<10	<1	56
4	ERK-96-116	280	<0.2	2.77	830	275	<5	2.74	<1	112	40	51	4.85	<10	1.83	799	4	0.08	8	1650	4	<5	<20	71	0.04	<10	131	<10	<1	48
5	ERK-96-117	10	<0.2	2.66	210	210	<5	4.97	<1	49	39	49	4.57	<10	1.71	890	1	0.14	6	1550	12	5	<20	130	0.09	<10	153	<10	1	67
6	ERK-96-118	>1000	2.2	2.97	3200	205	<5	2.83	<1	386	25	972	>10	<10	1.47	804	16	0.09	12	1180	16	<5	<20	73	0.06	<10	219	<10	<1	107
7	ERK-96-119	20	<0.2	2.65	115	195	<5	4.33	<1	22	21	59	4.81	<10	1.51	913	1	0.09	5	1030	6	<5	<20	100	0.13	<10	81	<10	4	48
8	ERK-96-120	>1000	2.4	3.12	5875	220	<5	1.64	<1	458	35	369	9.47	<10	1.71	893	12	0.06	12	1570	6	<5	<20	43	0.03	<10	146	<10	<1	58
9	ERK-96-121	805	0.2	2.49	410	205	<5	4.14	<1	82	40	92	4.87	<10	1.41	868	3	0.08	8	1550	6	<5	<20	102	0.03	<10	122	<10	<1	47
10	ERK-96-122	5	0.4	3.71	15	385	<5	4.60	<1	19	11	67	6.09	<10	1.83	1750	4	0.01	6	1770	6	<5	<20	98	0.03	<10	101	<10	<1	75
11	ERK-96-123	5	1.0	3.36	50	335	<5	6.18	13	21	23	95	6.37	<10	1.49	2369	7	<0.01	5	1530	36	<5	<20	136	0.03	<10	103	<10	<1	656
12	ERK-96-124	5	0.8	3.32	15	555	<5	6.81	3	20	22	79	5.73	<10	1.39	2382	5	0.01	8	1600	10	<5	<20	146	0.03	<10	103	<10	<1	130
13	ERK-96-125	5	1.0	4.13	35	445	<5	4.88	2	24	31	110	7.79	<10	2.14	1682	7	0.01	10	1730	20	<5	<20	117	0.03	<10	143	<10	<1	184
14	ERK-96-126	5	0.4	3.17	60	385	<5	9.74	<1	29	33	81	8.00	<10	1.58	3251	9	0.03	10	890	18	<5	<20	206	0.03	<10	172	<10	<1	70
15	ERK-96-127	5	0.6	3.27	25	715	5	3.94	3	22	34	50	7.04	<10	1.45	1430	8	0.02	10	900	48	<5	<20	118	0.04	<10	171	<10	<1	279
16	ERK-96-128	5	1.4	3.33	60	580	<5	1.58	3	26	40	111	8.17	<10	1.39	1600	18	0.01	12	1210	108	<5	<20	46	0.04	<10	168	<10	<1	280
17	ERK-96-129	15	1.0	3.25	35	435	<5	5.68	<1	21	66	88	7.92	<10	1.41	1802	5	0.04	18	1920	50	<5	<20	137	0.04	<10	122	<10	<1	98
18	ERK-96-130	5	3.8	3.93	310	535	5	1.55	8	32	54	126	>10	<10	1.96	1216	9	<0.01	14	1380	180	<5	<20	38	0.05	<10	182	<10	<1	703
19	ERK-96-131	5	1.2	3.66	45	280	<5	2.78	1	27	45	122	>10	<10	2.14	1497	10	<0.01	13	1590	64	<5	<20	67	0.03	<10	254	<10	<1	160

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS-5181

ECO-TECH LABORATORIES LTD.

CERTIFICATE OF ASSAY AS 96-5194

TEUTON RESOURCES CORPORATION
 509-675 W. HASTINGS STREET
 VANCOUVER, B.C.
 V6C 1N2

28-Aug-96

ATTENTION: DINO CREMONESE

No. of samples received: 49
Sample Type: Rock
PROJECT #: Treaty Creek
SHIPMENT #: 1
P.O.#: None Given
Samples submitted by: Alex Walus

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	As (%)	Pb (%)	Sb (%)	Zn (%)
3	A96-403	3.52	0.103	-	-	-	-	-	-	-
4	A96-404	2.88	0.084	-	-	-	-	-	-	-
5	A96-405	3.76	0.110	-	-	-	-	-	-	-
12	A96-412	-	-	47.2	1.38	-	-	-	-	-
13	A96-413	-	-	1110.0	32.37	-	-	10.80	-	-
14	A96-414	1.18	0.034	2445.0	71.30	-	-	45.10	1.37	3.31
16	A96-430	2.07	0.060	-	-	-	-	-	-	-
17	A96-431	1.61	0.047	31.6	0.92	-	-	-	-	-
18	A96-432	1.32	0.038	31.3	0.91	-	-	-	-	-
23	A96-437	-	-	69.9	2.04	-	-	3.37	-	-
25	A96-439	-	-	129.8	3.79	-	-	-	-	-
28	A96-442	6.40	0.187	1698.0	49.52	4.38	1.87	9.20	4.28	3.82
29	A96-443	-	-	85.3	2.49	-	-	-	-	-

QC/DATA:

Standard:

CD-1	-	-	-	-	-	-	0.66	-	3.57	-
CPb-I	-	-	631.0	18.40	0.25	-	-	-	-	4.46

XLS/96Teuton#5

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

27-Aug-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 8T4

ICP CERTIFICATE OF ANALYSIS - AS-5194

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 49
Sample Type: Rock
PROJECT #: Treaty Creek
SHIPMENT #: 1
P.O.#: None Given
Samples submitted by: Alex Wakus

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	A98-401	40	0.4	0.72	3980	55	<5	0.26	<1	9	32	60	3.29	<10	0.04	141	4	<0.01	4	1030	24	30	<20	8	<0.01	<10	25	<10	<1	34
2	A98-402	35	0.4	0.69	3910	55	<5	0.22	<1	10	28	57	3.23	<10	0.04	113	3	<0.01	4	950	24	30	<20	4	<0.01	<10	24	<10	<1	33
3	A98-403	>1000	6.4	0.28	745	405	<5	0.03	<1	<1	146	6	0.56	<10	0.02	25	5	<0.01	3	200	12	65	<20	8	<0.01	<10	11	<10	<1	4
4	A98-404	>1000	6.6	0.23	1495	55	<5	0.05	<1	2	162	39	1.18	<10	0.02	32	7	<0.01	3	610	14	40	<20	3	<0.01	<10	10	<10	<1	4
5	A98-405	>1000	9.8	0.26	2960	30	<5	0.22	<1	6	161	119	2.28	<10	0.01	36	7	<0.01	5	340	30	75	<20	5	<0.01	<10	10	<10	<1	18
6	A98-406	15	<0.2	2.49	1115	170	5	4.48	<1	48	26	39	>10	<10	1.13	2223	9	0.02	20	1640	22	20	<20	71	0.01	<10	304	<10	12	134
7	A98-407	15	<0.2	2.50	1165	95	15	4.30	<1	48	28	39	>10	<10	1.16	2159	9	0.02	18	1640	22	30	<20	64	0.01	<10	305	<10	12	132
8	A98-408	5	0.8	1.01	65	115	<5	3.28	1	12	20	67	4.36	<10	0.12	2128	3	<0.01	11	1240	46	10	<20	51	0.01	<10	26	<10	3	157
9	A98-409	5	3.6	1.20	245	550	<5	4.30	1	18	21	96	4.20	<10	0.13	4862	4	<0.01	17	1500	92	25	<20	62	0.02	<10	28	<10	6	333
10	A98-410	465	4.4	0.60	6575	265	<5	0.28	<1	23	21	66	5.23	<10	0.03	4244	5	<0.01	12	1050	392	80	<20	30	<0.01	<10	16	<10	2	557
11	A98-411	630	6.6	0.53	7870	305	<5	0.21	<1	15	27	443	5.45	<10	0.02	3405	5	<0.01	5	1330	1062	285	<20	29	<0.01	<10	14	<10	<1	653
12	A98-412	475	>30	0.58	7010	515	<5	0.47	<1	13	47	424	6.26	<10	0.03	>10000	9	<0.01	12	960	5682	500	<20	121	0.06	<10	13	<10	<1	1081
13	A98-413	805	>30	0.25	4430	25	<5	0.22	26	11	87	4229	5.08	<10	0.03	>10000	13	<0.01	10	470	>10000	5995	<20	23	0.05	<10	8	<10	<1	5909
14	A98-414	>1000	>30	0.07	5275	10	<5	0.10	262	5	25	7430	2.87	<10	<0.01	7189	<1	<0.01	4	370	>10000	>10000	<20	24	0.01	<10	2	<10	<1	>10000
15	A98-429	720	15.6	0.54	5050	355	<5	0.41	<1	8	38	230	3.72	<10	0.04	4034	7	<0.01	7	940	2126	305	<20	62	<0.01	<10	11	<10	1	1094
16	A98-430	>1000	25.4	0.46	7345	850	<5	0.81	<1	11	74	194	5.07	<10	0.04	>10000	24	<0.01	25	1050	1580	195	<20	93	0.04	<10	16	<10	5	2208
17	A98-431	>1000	>30	0.42	5985	740	<5	0.97	<1	10	132	357	4.36	<10	0.04	>10000	28	<0.01	25	900	1266	235	<20	105	0.03	<10	17	<10	4	1350
18	A98-432	>1000	>30	0.57	3260	345	<5	2.61	<1	8	153	221	3.06	<10	0.06	6643	13	<0.01	11	820	4184	140	<20	200	0.02	<10	14	<10	4	1522
19	A98-433	5	0.6	0.72	50	70	5	7.83	<1	5	117	24	2.81	<10	0.41	1192	6	<0.01	10	640	144	<5	<20	411	<0.01	<10	26	<10	3	35
20	A98-434	5	0.8	0.37	35	1740	5	>10	<1	<1	10	25	4.05	<10	7.63	2765	2	<0.01	1	350	38	15	<20	921	<0.01	<10	36	<10	<1	47
21	A98-435	110	25.2	0.10	165	110	<5	>10	<1	5	89	1416	4.97	<10	1.30	>10000	10	<0.01	4	<10	6604	15	<20	334	0.11	<10	17	<10	5	37
22	A98-436	115	14.4	0.09	515	65	<5	>10	<1	7	73	1949	5.57	<10	1.14	>10000	12	<0.01	4	<10	92	25	<20	554	0.11	<10	18	<10	4	32
23	A98-437	75	>30	0.05	225	85	<5	>10	23	4	72	434	1.87	<10	0.14	>10000	7	<0.01	5	40	>10000	25	<20	589	0.04	<10	7	<10	4	1668
24	A98-438	690	7.0	0.26	2275	160	5	>10	<1	9	55	58	6.81	<10	1.75	>10000	8	<0.01	6	270	104	25	<20	375	0.06	<10	49	<10	8	93
25	A98-439	520	>30	0.19	855	75	<5	>10	16	7	32	4070	2.94	10	0.18	>10000	4	<0.01	6	30	2200	445	<20	542	0.06	<10	51	<10	15	1437

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS-5194

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	A96-440	5	3.8	1.08	1215	400	<5	4.54	<1	19	22	241	4.80	<10	0.10	7328	5	<0.01	22	1420	90	75	<20	88	0.02	<10	26	<10	5	1491
27	A96-441	335	12.0	0.83	4505	405	<5	0.97	<1	22	25	279	5.02	<10	0.08	7075	6	<0.01	24	1800	456	165	<20	53	0.01	<10	20	<10	5	1478
28	A96-442	>1000	>30	0.12	>10000	25	<5	0.67	413	14	68	<1	8.31	<10	0.09	>10000	<1	<0.01	11	>10000	>10000	>10000	<20	61	<0.01	<10	7	<10	<1	>10000
29	A96-443	80	>30	0.74	2325	80	<5	8.97	<1	17	39	621	4.28	<10	0.62	6394	15	<0.01	21	1450	744	350	<20	263	0.01	<10	27	<10	6	1280
30	A96-444	30	26.2	0.86	1390	320	<5	4.15	<1	23	26	185	4.12	<10	0.31	3484	14	<0.01	28	2060	254	140	<20	93	<0.01	<10	33	<10	6	432
31	A96-445	45	14.2	0.85	1730	765	<5	6.23	<1	19	30	188	4.28	<10	0.35	3189	17	<0.01	27	1660	930	125	<20	164	<0.01	<10	29	<10	7	627
32	A96-446	15	3.0	1.21	435	105	<5	6.46	<1	21	14	192	4.74	<10	0.21	1298	8	<0.01	25	3170	54	35	<20	192	<0.01	<10	46	<10	11	194
33	A96-447	5	1.0	0.96	765	430	<5	8.42	<1	21	17	126	4.81	<10	0.25	1543	8	<0.01	28	1810	42	40	<20	293	<0.01	<10	36	<10	6	291
34	A96-448	5	0.2	2.96	265	170	<5	1.12	<1	27	15	212	7.57	<10	1.46	2098	3	0.03	10	2650	28	<5	<20	18	0.07	<10	183	<10	-6	-98
35	A96-449	10	0.4	1.89	135	140	<5	1.13	<1	23	20	123	5.89	<10	0.83	2141	3	0.02	9	2560	24	<5	<20	19	0.05	<10	144	<10	7	86
36	A96-450	5	0.4	1.71	300	155	<5	0.81	<1	23	20	175	5.67	<10	0.54	1757	2	0.02	8	2650	34	<5	<20	22	0.06	<10	132	<10	5	78
37	A96-451	5	0.8	1.35	720	175	<5	0.71	<1	30	9	184	5.32	<10	0.18	3069	4	0.01	13	3000	24	<5	<20	18	0.01	<10	94	<10	7	93
38	A96-452	10	0.4	1.99	2000	200	10	1.63	<1	50	16	57	>10	<10	0.35	2718	10	<0.01	21	2280	34	<5	<20	23	0.03	<10	251	<10	18	153
39	A96-453	5	<0.2	2.87	950	170	15	1.36	<1	62	27	42	>10	<10	1.49	2436	4	0.03	30	1930	28	<5	<20	27	0.21	<10	340	<10	18	153
40	A96-454	5	<0.2	3.70	220	130	20	1.92	<1	54	40	46	>10	<10	2.83	1497	<1	0.06	28	1750	30	<5	<20	34	0.39	<10	329	<10	9	110
41	A96-455	195	4.0	2.47	1045	120	<5	0.38	<1	10	9	42	2.42	<10	2.12	2337	2	<0.01	5	890	176	30	<20	13	<0.01	<10	23	<10	6	913
42	A96-456	85	0.8	2.28	1080	115	<5	0.71	<1	11	5	41	2.10	10	1.92	1747	3	<0.01	6	870	74	25	<20	20	<0.01	<10	24	<10	8	363
43	A96-457	50	0.6	2.13	790	115	<5	2.01	<1	7	15	33	2.64	<10	1.96	2039	4	<0.01	5	560	56	35	<20	20	<0.01	<10	19	<10	7	248
44	A96-458	330	0.8	2.79	600	115	<5	1.89	<1	10	5	35	2.47	10	2.86	2033	3	<0.01	5	830	76	35	<20	38	<0.01	<10	28	<10	7	137
45	A96-459	555	1.6	2.48	935	110	5	3.14	<1	9	7	36	3.54	<10	2.09	2325	6	<0.01	6	760	74	45	<20	46	<0.01	<10	25	<10	9	284
46	A96-460	305	2.0	1.58	1695	175	<5	0.77	<1	17	16	98	3.61	<10	0.54	2704	14	<0.01	19	1640	106	70	<20	49	<0.01	<10	52	<10	10	775
47	A96-461	510	3.2	1.24	1310	145	<5	1.42	<1	17	15	103	3.85	<10	0.28	1735	12	<0.01	17	1550	160	30	<20	56	<0.01	<10	41	<10	9	464
48	A96-462	570	4.0	1.33	1190	200	<5	4.90	<1	16	19	99	4.27	<10	0.47	3083	9	<0.01	16	1450	162	25	<20	86	<0.01	<10	54	<10	7	260
49	A96-463	180	1.8	1.14	525	150	<5	5.67	<1	15	13	99	3.46	<10	0.66	2267	13	<0.01	16	1940	104	30	<20	157	<0.01	<10	55	<10	9	255

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS-5194

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
------	-------	---------	----	------	----	----	----	------	----	----	----	----	------	----	------	----	----	------	----	---	----	----	----	----	------	---	---	---	---	----

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 8T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AS-5202

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 18

Sample Type: Rock

PROJECT #: Clone

SHIPMENT #: S96-36

P.O.#: None Given

Samples submitted by: David Hick

Values in ppm unless otherwise reported

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	D96-229	5	1.4	1.04	55	75	<5	3.22	2	11	109	104	3.89	<10	0.48	1101	8	<0.01	115	1430	48	<5	<20	78	<0.01	<10	25	<10	<1	147
2	D96-230	10	2.2	2.39	60	60	<5	4.69	2	23	28	106	6.33	<10	1.47	2027	11	<0.01	8	1520	38	<5	<20	88	<0.01	<10	70	<10	<1	161
3	D96-231	15	1.8	2.86	25	70	<5	4.79	4	39	25	126	8.30	<10	1.66	2242	9	<0.01	13	1560	80	<5	<20	82	<0.01	<10	79	<10	<1	401
4	D96-232	45	2.2	2.22	60	95	<5	4.50	10	28	25	120	6.19	<10	1.09	2172	19	<0.01	13	1700	148	<5	<20	82	<0.01	<10	82	<10	<1	614
5	D96-233	15	1.4	1.78	25	90	<5	>10	13	26	14	91	4.08	<10	1.02	3171	15	<0.01	7	1550	100	<5	<20	222	<0.01	<10	52	<10	3	892
6	D96-234	5	0.6	2.48	10	85	<5	8.90	2	23	20	74	5.71	<10	1.68	2608	8	<0.01	8	1540	28	<5	<20	208	<0.01	<10	85	<10	<1	115
7	D96-235	5	1.2	1.66	40	70	<5	6.28	5	22	34	85	4.77	<10	1.17	1854	7	<0.01	8	1330	64	<5	<20	142	<0.01	<10	73	<10	<1	334
8	D96-236	20	2.0	2.63	70	85	<5	5.05	19	25	22	148	6.67	<10	1.79	1623	6	<0.01	8	1630	84	<5	<20	115	<0.01	<10	117	<10	<1	1144
9	D96-237	25	1.8	2.63	60	100	<5	6.56	<1	27	24	156	6.92	<10	1.79	1987	6	<0.01	9	1620	46	<5	<20	146	<0.01	<10	119	<10	<1	128
10	D96-238	15	0.4	3.12	50	105	10	4.70	<1	32	74	85	7.77	<10	2.39	1384	6	<0.01	20	1850	34	<5	<20	137	<0.01	<10	162	<10	<1	88
11	D96-239	5	0.6	2.52	40	95	<5	6.78	2	29	18	114	6.93	<10	1.78	1695	8	0.01	12	1590	52	<5	<20	220	<0.01	<10	126	<10	<1	139
12	D96-240	5	0.8	2.15	20	105	<5	6.34	2	15	8	58	5.12	<10	1.29	2129	7	<0.01	4	1670	46	<5	<20	228	<0.01	<10	60	<10	<1	134
13	D96-241	10	0.8	2.61	15	130	<5	7.89	<1	17	18	74	5.51	<10	1.35	1744	4	<0.01	7	1560	20	<5	<20	242	<0.01	<10	68	<10	<1	107
14	D96-242	90	1.4	2.01	220	45	<5	5.43	<1	29	27	142	8.57	<10	0.60	1389	8	<0.01	15	1660	54	<5	<20	102	0.01	<10	52	<10	<1	109
15	D96-243	60	0.6	1.50	15	215	<5	>10	<1	18	13	96	3.52	<10	0.51	1434	3	<0.01	4	1540	26	<5	<20	200	<0.01	<10	32	<10	3	57
16	D96-244	50	<0.2	1.28	30	310	<5	7.98	<1	23	11	64	4.25	<10	0.32	1085	3	<0.01	6	1940	16	<5	<20	159	0.03	<10	49	<10	4	56
17	D96-245	175	0.2	0.82	45	960	<5	>10	<1	61	10	203	2.26	<10	0.25	1313	1	<0.01	2	1530	12	<5	<20	291	<0.01	<10	20	<10	3	41
18	D96-246	150	<0.2	1.78	65	390	<5	6.06	<1	77	11	199	6.01	<10	0.78	907	5	0.01	11	2020	14	<5	<20	159	0.03	<10	73	<10	2	109

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS-5202

ECO-TECH LABORATORIES LTD.

02-Sep-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 8T4

ICP CERTIFICATE OF ANALYSIS - AS-5203

TEUTON RESOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V8C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 17
Sample Type: Rock
PROJECT #: Clone
SHIPMENT #: S96-37
P.O.#: None Given
Samples submitted by: David Hick

Values in ppm unless otherwise reported

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Cs %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	D96-247	25	0.8	1.03	75	180	<5	8.37	<1	25	58	117	5.49	<10	2.98	1566	5	0.01	33	1420	2	5	<20	356	<0.01	<10	41	<10	5	40
2	D96-248	40	0.2	0.78	15	85	<5	1.08	<1	9	77	20	2.25	<10	0.37	355	2	<0.01	8	880	6	<5	<20	18	<0.01	<10	22	<10	1	29
3	D96-249	25	0.8	1.32	25	90	<5	3.29	<1	15	113	82	3.22	<10	0.91	824	5	<0.01	18	1020	28	<5	<20	50	<0.01	<10	52	<10	4	130
4	D96-250	10	0.8	1.82	40	70	<5	4.15	<1	27	91	67	4.39	<10	1.22	1295	4	<0.01	19	1110	8	<5	<20	59	<0.01	<10	55	<10	2	36
5	D96-251	15	0.4	0.98	30	50	<5	6.56	<1	14	86	58	2.33	<10	0.53	883	5	<0.01	8	630	8	<5	<20	64	<0.01	<10	25	10	6	20
6	D96-252	115	1.6	1.55	100	90	<5	5.84	<1	12	79	158	3.89	<10	0.64	1212	5	<0.01	11	950	8	<5	<20	59	<0.01	<10	41	<10	4	37
7	D96-253	160	3.8	2.71	255	65	<5	2.80	<1	27	113	195	8.08	<10	2.23	656	6	0.01	33	1050	22	<5	<20	59	<0.01	<10	124	<10	<1	40
8	D96-254	15	0.8	4.05	110	65	<5	4.70	<1	32	117	204	8.10	<10	3.84	974	5	0.02	31	1690	8	<5	<20	92	0.02	<10	212	<10	<1	54
9	D96-255	5	0.2	1.27	15	95	<5	5.11	<1	11	89	70	2.73	<10	1.45	880	2	0.02	15	1070	6	5	<20	213	<0.01	<10	40	<10	3	31
10	D96-256	5	0.4	1.45	30	145	<5	5.70	<1	15	37	63	4.16	<10	1.63	1145	4	0.01	12	1420	6	<5	<20	208	<0.01	<10	46	<10	4	42
11	D96-257	315	0.4	1.33	45	120	<5	2.29	<1	16	92	79	3.64	<10	1.17	579	4	<0.01	15	980	20	5	<20	71	<0.01	<10	39	<10	1	54
12	D96-258	95	0.8	1.23	250	100	<5	2.21	<1	15	87	101	3.48	<10	0.96	590	5	<0.01	12	1030	14	<5	<20	67	<0.01	<10	33	<10	1	31
13	D96-259	15	0.8	0.97	45	105	<5	5.96	<1	16	83	93	4.49	<10	1.81	1115	5	0.01	17	1110	14	<5	<20	223	<0.01	<10	37	<10	4	27
14	D96-260	20	0.8	3.39	70	75	<5	8.68	<1	22	87	173	6.71	<10	2.83	1164	3	0.02	23	1410	10	<5	<20	323	0.01	<10	174	<10	2	42
15	D96-261	5	<0.2	3.32	25	75	<5	7.81	<1	24	88	106	6.07	<10	3.36	1216	<1	0.03	26	1380	10	<5	<20	272	0.09	<10	201	<10	3	41
16	D96-262	10	<0.2	3.43	35	70	<5	5.34	<1	27	97	136	6.56	<10	3.52	1095	2	0.02	27	1400	12	<5	<20	120	0.10	<10	220	<10	2	38
17	D96-263	5	<0.2	3.48	20	65	<5	6.44	<1	29	101	116	6.71	<10	3.43	1205	1	0.02	30	1610	6	<5	<20	130	0.10	<10	235	<10	3	39

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS-5203

ECO-TECH LABORATORIES LTD.



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5204

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

5-Sep-96

ATTENTION: DINO CREMONESE

No. of samples received: 16
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-38
P.O.#: NONE GIVEN
Samples submitted by: DAVID HICK


ET #.	Tag #	Au (g/t)	Au (oz/t)	Co (%)	As (%)
13	D96-288	1.24	0.036	0.140	2.04
15	D96-290	2.49	0.073	0.068	-
16	D96-291	76.11	2.220	0.067	1.25

QC/DATA:

Standard:

Sula	-	-	0.041		
CD-I	-	-	-	0.66	

XLS/96Teuton#5

per 
ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

3-Sep-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5204

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 16
Sample Type: Rock
PROJECT #: Clone
SHIPMENT #: S96-38
P.O.#: None Given
Samples submitted by: David Hick

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	D96-276	5	1.6	1.01	<5	495	<5	4.98	6	11	23	101	4.68	<10	0.38	1840	3	<0.01	5	530	62	<5	<20	120	0.04	<10	100	<10	<1	383
2	D96-277	5	1.2	1.69	<5	635	<5	3.79	4	19	19	41	5.94	<10	0.44	1842	4	<0.01	7	1460	30	<5	<20	70	0.03	<10	99	<10	<1	295
3	D96-278	5	0.4	1.22	<5	400	5	4.52	3	12	17	24	5.29	<10	0.25	1906	3	<0.01	4	1310	26	<5	<20	74	0.04	<10	123	<10	<1	191
4	D96-279	10	1.0	2.16	<5	240	10	3.09	2	19	20	46	6.77	<10	0.58	2137	4	<0.01	7	1330	68	<5	<20	45	0.03	<10	102	<10	<1	232
5	D96-280	10	11.4	2.15	15	80	<5	1.67	7	13	17	65	5.95	<10	0.74	1330	7	<0.01	4	1070	266	<5	<20	26	<0.01	<10	46	<10	<1	446
6	D96-281	5	4.0	2.72	20	100	<5	4.23	3	20	19	49	6.25	<10	1.22	2700	5	<0.01	8	1210	76	<5	<20	67	<0.01	<10	78	<10	<1	263
7	D96-282	10	18.0	2.42	30	50	<5	8.16	16	25	18	296	7.50	<10	1.36	4459	6	<0.01	10	790	356	<5	<20	130	0.01	<10	122	<10	<1	807
8	D96-283	80	23.0	2.66	25	75	<5	8.81	11	24	19	342	7.38	<10	1.51	4663	7	<0.01	8	870	172	10	<20	138	0.01	<10	113	<10	<1	526
9	D96-284	30	3.8	2.63	60	80	<5	5.56	10	21	22	98	6.39	<10	1.17	3327	15	<0.01	10	1130	112	<5	<20	71	<0.01	<10	99	<10	<1	572
10	D96-285	5	1.4	2.52	20	220	<5	8.63	6	11	15	48	5.78	<10	1.11	3739	7	<0.01	5	750	36	<5	<20	117	<0.01	<10	58	<10	<1	328
11	D96-286	180	1.4	1.47	4600	125	<5	2.52	<1	167	21	86	4.12	<10	0.42	1372	4	<0.01	12	1660	156	5	<20	31	<0.01	<10	46	<10	<1	280
12	D96-287	130	3.0	1.73	245	75	<5	>10	<1	26	11	913	6.06	<10	1.10	2715	4	<0.01	12	890	28	<5	<20	238	<0.01	<10	59	<10	1	101
13	D96-288	>1000	0.8	2.93	>10000	85	<5	5.66	<1	1148	26	156	7.38	<10	2.32	1618	12	0.02	8	1360	28	<5	<20	135	0.01	<10	95	<10	<1	497
14	D96-289	130	<0.2	4.31	1285	90	<5	2.36	<1	81	29	326	8.73	<10	3.65	956	6	0.02	10	1840	14	<5	<20	74	0.01	<10	154	<10	<1	60
15	D96-290	>1000	1.4	3.89	5515	65	<5	3.48	<1	566	7	2145	>10	<10	3.05	973	13	0.01	9	1550	38	<5	<20	95	0.01	<10	127	<10	<1	61
16	D96-291	>1000	13.2	2.75	>10000	70	<5	7.77	<1	605	<1	448	>10	<10	2.12	1479	121	0.02	13	1080	326	<5	<20	243	0.01	<10	89	<10	<1	794

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
QC/DATA:																															
<i>Resplit:</i>																															
R/S 1	D96-276	5	1.6	1.07	<5	545	<5	5.01	6	12	28	96	4.86	<10	0.36	1842	2	<0.01	5	590	62	<5	<20	125	0.04	<10	103	<10	<1	413	
<i>Standard:</i>																															
GEO'96		150	1.2	1.69	65	145	<5	1.78	<1	17	64	75	3.76	<10	0.89	670	<1	0.02	23	690	22	<5	<20	62	0.11	<10	75	<10	3	71	

df/5203
XLS/96Teuton


 ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer



ASSAYING
 GEOCHEMISTRY
 ANALYTICAL CHEMISTRY
 ENVIRONMENTAL TESTING

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
 Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5207

TEUTON RESOURCES CORPORATION
 509-675 W. HASTINGS STREET
 VANCOUVER, B.C.
 V6C 1N2

6-Sep-96

ATTENTION: DINO CREMONESE

No. of samples received: 23
Sample Type: Rock
PROJECT #: Clone
SHIPMENT #: S96-39
P.O.#: None Given
Samples submitted by: Sherry Chandler


ET #.	Tag #	Au (g/t)	Au (oz/t)	As (%)	Co (%)
3	ERK-96-137	11.62	0.339	-	-
6	ERK-96-139	4.62	0.135	-	0.099
9	ERK-96-142	1.67	0.049	-	0.025
10	ERK-96-143	19.78	0.577	3.33	0.488

QC DATA:

standard:

CD-I	-	-	0.66	-
------	---	---	------	---

XLS/96Teuton#5


ECO-TECH LABORATORIES LTD
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5207

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 23

Sample Type: Rock

PROJECT #: Clone

SHIPMENT #: S96-39

P.O.#: None Given

Samples submitted by: Sherry Chandler

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	ERK-96-134	10	<0.2	2.72	55	45	<5	2.88	<1	23	32	113	6.13	<10	2.55	1172	3	0.06	8	1880	16	<5	80	57	0.11	<10	225	<10	2	64
2	ERK-96-135	115	<0.2	4.13	80	45	<5	6.08	<1	53	23	169	8.74	<10	3.93	1736	2	0.02	21	1680	16	<5	180	104	0.19	<10	315	<10	<1	91
3	ERK-96-136	>1000	11.6	3.84	4565	75	<5	2.50	<1	139	15	3569	>10	<10	2.96	1204	11	0.02	11	1570	76	<5	200	53	0.09	<10	196	<10	<1	307
4	ERK-96-137	105	<0.2	3.93	125	45	<5	3.00	<1	36	13	165	8.00	<10	3.97	1217	2	0.03	10	2420	18	<5	160	85	0.18	<10	285	<10	2	60
5	ERK-96-138	5	<0.2	1.87	70	100	<5	1.62	<1	46	31	104	3.90	<10	1.18	773	1	0.03	4	1530	16	<5	40	32	0.07	<10	59	<10	5	90
6	ERK-96-139	>1000	3.2	2.21	1955	205	<5	1.01	<1	962	18	1950	>10	<10	1.65	946	9	0.01	2	1660	26	<5	240	22	0.04	<10	124	<10	<1	248
7	ERK-96-140	10	<0.2	4.20	60	105	<5	0.66	<1	47	53	193	8.44	<10	3.61	1329	1	0.03	18	2030	36	<5	140	16	0.17	<10	220	<10	4	98
8	ERK-96-141	35	<0.2	4.86	55	110	<5	0.70	<1	32	39	148	>10	<10	4.34	1072	1	0.02	12	2240	24	<5	200	13	0.18	<10	258	<10	<1	57
9	ERK-96-142	>1000	<0.2	3.71	260	95	<5	1.18	<1	220	21	371	9.38	<10	3.10	755	3	<0.01	8	2220	24	<5	200	24	0.12	<10	167	<10	1	49
10	ERK-96-143	>1000	3.4	3.22	>10000	55	<5	0.38	<1	4354	12	1146	>10	<10	2.53	630	55	0.01	<1	1440	56	<5	300	25	0.03	<10	216	<10	<1	60
11	AR-96-03	45	<0.2	2.25	100	100	<5	1.59	<1	51	80	108	5.27	<10	1.68	464	<1	0.12	29	2000	26	<5	80	69	0.22	<10	123	<10	3	57
12	AR-96-04	130	<0.2	2.93	150	85	<5	4.41	<1	54	75	109	5.09	<10	1.33	533	<1	0.32	43	2100	38	<5	100	167	0.18	<10	83	<10	1	48
13	AR-96-05	5	<0.2	2.83	5	70	5	1.62	<1	38	79	105	7.35	<10	1.74	855	<1	0.06	15	1630	20	<5	160	40	0.39	<10	210	<10	3	68
14	AR-96-06	10	<0.2	3.27	20	75	<5	2.10	<1	32	48	95	7.14	<10	2.35	924	<1	0.05	12	2390	24	<5	140	49	0.27	<10	232	<10	5	73
15	AR-96-07	5	<0.2	2.48	<5	75	5	2.17	<1	26	49	69	5.41	<10	1.51	917	<1	0.07	13	1860	22	<5	100	42	0.31	<10	186	<10	5	63
16	AR-96-08	10	0.8	0.60	50	150	<5	>10	<1	15	32	21	6.45	<10	1.35	2572	7	0.01	10	1060	8	<5	140	328	<0.01	<10	63	<10	2	39
17	AR-96-09	5	0.8	0.91	20	135	<5	8.15	<1	14	23	73	4.57	<10	0.26	795	5	0.03	6	2000	18	<5	100	255	<0.01	<10	42	<10	2	29
18	AR-96-10	5	<0.2	3.41	<5	70	<5	4.99	<1	33	26	122	7.18	<10	2.90	1200	<1	0.04	14	1890	22	<5	180	157	0.22	<10	236	<10	3	69
19	AR-96-11	15	0.4	0.19	1505	65	<5	0.07	<1	15	184	20	3.42	<10	0.03	1113	8	<0.01	11	360	148	10	40	5	<0.01	<10	17	10	5	102
20	AR-96-12	10	<0.2	1.44	10	60	<5	0.68	<1	22	28	93	4.70	<10	1.23	732	<1	0.05	3	2390	18	<5	100	14	0.19	<10	158	20	4	29
21	AR-96-13	5	<0.2	1.57	15	10	5	1.79	<1	15	142	11	2.67	<10	0.90	780	<1	0.02	7	890	18	<5	20	27	0.20	<10	82	10	1	34
22	AR-96-14	5	<0.2	0.08	10	50	<5	2.80	50	4	183	16	0.89	<10	0.02	247	6	<0.01	4	230	428	<5	<20	48	<0.01	<10	5	<10	<1	5532
23	AR-96-15	10	0.8	0.11	15	25	5	0.05	2	4	257	9	3.59	<10	<0.01	59	16	<0.01	7	50	154	<5	40	1	<0.01	<10	5	<10	<1	119

Et #. Tag # Au(ppb) Ag Al % As Ba BI Ca % Cd Co Cr Cu Fe % La Mg % Mn Mo Na % Ni P Pb Sb Sn Sr Ti % U V W Y Zn

QC/DATA:**Resplit:**

R/S 1 ERK-96-134 10 <0.2 2.85 60 45 <5 3.09 <1 25 31 113 6.67 <10 2.63 1265 3 0.05 8 1960 18 <5 120 57 0.11 <10 235 <10 2 64


Repeat:


1 ERK-96-134 15 <0.2 2.83 60 45 <5 3.05 <1 24 35 116 6.47 <10 2.63 1229 3 0.05 7 2120 22 <5 100 58 0.12 <10 235 <10 2 61
 10 ERK-96-143 >1000 3.4 3.46 >10000 55 <5 0.41 <1 4597 13 1226 >10 <10 2.68 672 58 0.01 <1 1510 62 <5 360 26 0.03 <10 233 <10 <1 65
 17 AR-96-09 5 -

Standard:

GEO'96 150 1.4 1.93 65 155 <5 1.92 <1 20 68 81 4.31 <10 0.99 711 <1 0.03 26 820 24 <5 80 70 0.14 <10 84 <10 3 76
 GEO'96 150 -

df/5206
 XLS/96Teuton#5


 ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5223

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

11-Sep-96

ATTENTION: DINO CREMONESE

No. of samples received: 59
Sample Type: CORE
PROJECT #: TREATY CREEK
SHIPMENT #: NONE GIVEN
P.O.#: NONE GIVEN
Samples submitted by: ALEX WALUS

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
52	A96-515	-	-	36.1	1.053
53	A96-516	1.97	0.057	33.9	0.989
54	A96-517	1.94	0.057	35.8	1.044
59	A96-541	1.44	0.042	62.9	1.834

QC/DATA:

Standard:

CPb-I - - 630.0 18.373

XLS/96Teuton#7


ECO-TECH LABORATORIES LTD.

per Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

7-Sep-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5223

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE


No. of samples received: 59
Sample Type: CORE
PROJECT #: TREATY CREEK
SHIPMENT #: NONE GIVEN
P.O.#: NONE GIVEN
Samples submitted by: ALEX WALUS

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	A96-464	30	1.6	0.72	385	130	<5	3.89	<1	17	14	111	4.60	<10	0.24	2285	14	<0.01	18	1880	76	15	<20	76	<0.01	<10	72	<10	5	143
2	A96-465	5	0.8	0.56	325	85	<5	1.10	<1	16	15	103	4.11	<10	0.10	1089	5	0.02	14	1120	30	<5	<20	25	<0.01	<10	45	<10	6	69
3	A96-466	5	0.4	0.35	135	65	<5	0.51	<1	5	37	27	3.87	<10	0.03	342	7	0.01	3	240	14	<5	<20	14	<0.01	<10	3	<10	<1	26
4	A96-467	60	<0.2	1.58	350	65	<5	2.62	<1	11	26	97	3.07	<10	2.02	1639	10	0.01	19	3170	18	15	<20	141	<0.01	<10	151	<10	5	51
5	A96-468	530	1.0	1.00	1570	45	<5	5.08	<1	7	43	47	1.89	<10	1.88	1980	6	<0.01	8	520	22	25	<20	135	<0.01	<10	50	<10	2	44
6	A96-469	80	0.4	0.95	180	45	<5	>10	<1	4	11	18	1.00	<10	1.64	1501	4	<0.01	3	350	24	20	<20	715	<0.01	<10	82	<10	2	59
7	A96-470	145	3.0	2.10	1375	110	<5	1.88	<1	11	15	85	3.58	<10	2.72	2359	9	<0.01	11	1150	372	60	<20	61	<0.01	<10	64	<10	5	303
8	A96-471	175	4.8	1.63	385	100	<5	0.59	<1	14	26	122	3.99	<10	1.22	1388	7	0.01	17	1460	1010	15	<20	21	<0.01	<10	56	<10	6	807
9	A96-472	5	0.6	1.18	165	45	<5	0.36	<1	14	22	47	3.46	<10	0.90	693	5	<0.01	16	1090	68	5	<20	10	<0.01	<10	30	<10	3	110
10	A96-473	55	1.2	1.30	305	55	<5	0.46	<1	14	16	66	3.74	<10	1.00	842	4	<0.01	14	1250	90	10	<20	14	<0.01	<10	30	<10	3	141
11	A96-474	260	23.0	1.49	745	85	<5	0.53	<1	14	26	80	3.81	<10	1.07	1222	6	<0.01	13	1170	1202	20	<20	12	<0.01	<10	38	<10	4	249
12	A96-475	45	0.8	1.66	215	75	<5	0.65	<1	12	35	63	3.47	<10	1.39	1037	4	0.02	14	1200	70	5	<20	19	<0.01	<10	64	<10	4	113
13	A96-476	10	1.2	1.34	180	75	<5	0.54	<1	14	30	91	3.79	<10	0.75	901	12	0.02	16	1400	56	<5	<20	38	<0.01	<10	55	<10	5	107
14	A96-477	10	1.6	1.05	215	100	<5	5.45	<1	11	15	81	3.01	<10	0.92	1207	13	0.01	11	1580	58	10	<20	171	<0.01	<10	50	<10	4	72
15	A96-478	20	1.2	1.05	280	135	<5	9.16	<1	11	13	73	3.66	<10	0.90	1905	9	<0.01	11	1070	58	10	<20	257	<0.01	<10	62	<10	4	122
16	A96-479	30	1.4	1.12	710	105	<5	1.16	<1	17	13	100	4.29	<10	0.49	1341	17	<0.01	18	1180	86	5	<20	25	<0.01	<10	36	<10	4	315
17	A96-480	80	1.6	1.26	410	80	<5	0.55	<1	16	23	67	3.92	<10	0.73	1021	6	0.01	16	1140	90	<5	<20	16	<0.01	<10	43	<10	4	198
18	A96-481	15	1.2	1.40	290	80	<5	0.44	<1	16	28	63	4.15	<10	0.91	1153	5	0.01	17	1130	74	<5	<20	13	<0.01	<10	64	<10	5	93
19	A96-482	10	0.6	1.26	265	85	<5	0.37	<1	16	26	81	4.20	<10	0.57	1042	5	0.02	15	1350	32	<5	<20	14	<0.01	<10	59	<10	5	79
20	A96-483	5	<0.2	1.62	25	360	<5	2.06	<1	11	9	28	4.20	<10	0.84	725	3	0.01	4	2150	12	<5	<20	22	<0.01	<10	72	<10	3	49
21	A96-484	5	<0.2	1.64	25	330	<5	2.08	<1	12	9	29	4.27	<10	0.86	736	4	0.01	4	2160	12	<5	<20	19	<0.01	<10	73	<10	3	50
22	A96-485	5	<0.2	1.72	75	140	<5	1.91	<1	13	14	32	4.36	<10	1.00	768	4	0.01	4	2240	12	<5	<20	17	<0.01	<10	86	<10	3	56
23	A96-486	10	<0.2	2.85	230	95	10	1.22	<1	31	48	31	8.33	<10	2.04	1314	6	0.01	21	1540	18	<5	<20	6	<0.01	<10	205	<10	5	82
24	A96-487	525	0.4	2.27	250	120	5	0.97	<1	22	24	56	6.53	<10	1.47	1372	4	<0.01	11	1830	22	<5	<20	8	0.02	<10	146	<10	3	68
25	A96-488	220	2.8	2.83	905	120	<5	0.46	<1	19	20	91	5.90	<10	2.44	2631	5	0.01	12	1470	334	<5	<20	3	<0.01	<10	87	<10	3	216

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC/DATA:																														
<i>Resplit:</i>																														
1	A96-464	25	1.6	0.81	385	130	<5	4.00	<1	18	16	113	4.78	<10	0.24	2354	14	<0.01	19	2050	82	10	<20	77	<0.01	<10	75	<10	6	154
36	A96-499	5	<0.2	0.80	90	265	5	4.06	<1	13	9	5	4.57	<10	0.13	1142	4	<0.01	5	2070	8	<5	<20	10	<0.01	<10	52	<10	2	48
<i>Repeat:</i>																														
1	A96-464	40	1.6	0.74	390	130	<5	3.99	<1	18	14	115	4.76	<10	0.25	2356	14	<0.01	18	1950	80	15	<20	78	<0.01	<10	74	<10	5	149
10	A96-473	60	1.0	1.27	295	55	<5	0.45	<1	13	16	65	3.67	<10	0.98	823	4	<0.01	13	1220	90	10	<20	15	<0.01	<10	29	<10	3	139
19	A96-482	10	0.6	1.27	255	85	<5	0.38	<1	16	26	82	4.24	<10	0.57	1051	5	0.02	17	1360	34	<5	<20	15	<0.01	<10	60	<10	5	80
36	A96-499	5	0.2	0.73	95	320	<5	4.06	<1	14	9	7	4.65	<10	0.13	1259	4	<0.01	5	2080	6	<5	<20	11	<0.01	<10	52	<10	3	50
45	A96-508	35	<0.2	2.40	955	250	5	0.82	<1	32	24	66	8.36	<10	1.45	1284	5	0.01	21	1410	18	<5	<20	7	0.06	<10	218	<10	6	75
<i>Standard:</i>																														
GEO'96		140	0.8	1.43	70	150	<5	1.89	<1	15	50	79	3.90	<10	0.98	691	<1	0.01	19	670	20	<5	<20	57	0.09	<10	72	<10	4	70
GEO'96		145	0.8	1.36	65	160	<5	1.90	<1	15	77	57	4.01	<10	0.95	653	<1	<0.01	19	650	20	<5	<20	59	0.08	<10	79	<10	6	72

df/5247
XLS/96Teuton


ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 8T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AS-5224

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 19

Sample Type: ROCK

PROJECT #: CLONE

SHIPMENT #: S96-40

P.O.#: NONE GIVEN

Samples submitted by: DAVID HICK

Values in ppm unless otherwise reported

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	D96-292	5	2.8	1.85	210	40	<5	0.81	<1	26	19	124	8.59	<10	0.80	839	12	<0.01	4	1520	78	<5	<20	13	<0.01	<10	35	<10	<1	253
2	D96-293	5	0.8	0.68	20	130	<5	>10	<1	6	12	13	1.98	<10	0.40	3384	1	<0.01	1	570	32	<5	<20	279	<0.01	<10	12	<10	6	37
3	D96-294	40	1.2	2.41	65	30	<5	5.78	2	28	22	174	8.49	<10	2.08	1487	9	<0.01	5	1070	36	<5	<20	88	<0.01	<10	97	<10	<1	158
4	D96-295	35	5.6	3.19	105	40	<5	2.18	9	38	37	209	>10	<10	2.76	1025	10	<0.01	11	1300	358	<5	<20	32	<0.01	<10	158	<10	<1	657
5	D96-296	5	2.4	3.20	<5	295	<5	3.32	1	33	18	804	7.91	<10	2.13	1328	5	<0.01	6	1410	22	<5	<20	44	<0.01	<10	104	<10	<1	321
6	D96-297	10	0.4	3.73	<5	165	<5	1.44	<1	51	53	120	9.79	<10	2.83	1412	7	<0.01	15	1700	28	<5	<20	19	<0.01	<10	142	<10	<1	330
7	D96-298	10	1.8	2.47	<5	90	<5	3.35	<1	21	41	405	7.89	<10	1.80	1108	8	<0.01	13	1850	20	<5	<20	73	<0.01	<10	97	<10	<1	203
8	D96-299	5	0.6	2.48	<5	100	<5	3.41	<1	25	29	263	6.69	<10	1.75	1189	5	<0.01	12	1870	14	<5	<20	79	<0.01	<10	82	<10	<1	149
9	D96-300	15	1.4	3.70	5	50	<5	1.14	4	46	26	404	>10	<10	2.33	1569	11	<0.01	10	940	74	<5	<20	24	<0.01	<10	127	<10	<1	392
10	D96-301	25	1.2	2.45	10	70	<5	0.58	<1	26	20	145	5.57	<10	2.28	1013	4	<0.01	8	1540	124	<5	<20	43	<0.01	<10	106	<10	<1	325
11	D96-302	5	<0.2	3.49	<5	85	<5	4.35	<1	20	13	101	9.12	<10	2.52	1440	6	<0.01	5	1920	<2	<5	<20	113	0.02	<10	183	<10	<1	77
12	D96-303	5	0.4	2.18	<5	60	<5	3.74	1	37	23	123	7.15	<10	1.35	1196	7	<0.01	7	1670	20	<5	<20	83	<0.01	<10	93	<10	<1	194
13	D96-304	5	1.6	1.89	<5	155	<5	5.93	<1	22	24	43	4.80	<10	1.36	1643	5	<0.01	4	1190	14	<5	<20	123	<0.01	<10	68	<10	<1	176
14	D96-305	5	<0.2	0.60	<5	855	<5	6.88	<1	3	23	1	2.75	<10	0.24	1666	2	<0.01	1	1190	4	<5	<20	149	0.02	<10	15	<10	3	42
15	D96-306	5	0.6	1.55	50	50	<5	9.48	7	17	16	53	4.66	<10	0.99	2299	11	<0.01	4	1080	30	<5	<20	142	<0.01	<10	40	<10	2	388
16	D96-307	5	0.2	1.87	<5	915	<5	1.64	4	17	26	93	6.23	<10	1.42	858	4	<0.01	10	1520	26	<5	<20	62	0.02	<10	85	<10	<1	258
17	D96-308	30	1.0	1.44	<5	455	<5	1.83	4	21	21	730	8.07	<10	0.87	795	6	<0.01	6	990	152	<5	<20	70	0.05	<10	82	<10	<1	375
18	D96-309	205	<0.2	2.51	<5	70	<5	3.38	<1	16	10	51	6.55	<10	1.88	988	3	<0.01	7	1980	<2	<5	<20	139	<0.01	<10	99	<10	<1	58
19	D96-310	5	0.6	3.07	<5	60	<5	0.88	<1	40	24	136	8.03	<10	2.36	919	6	<0.01	6	1360	18	<5	<20	24	<0.01	<10	99	<10	<1	135

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS-5224

ECO-TECH LABORATORIES LTD.



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5228

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2


9-Sep-96

ATTENTION: DINO CREMONESE

No. of samples received: 31
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-41
P.O.#: NONE GIVEN
Samples submitted by: DAVID HICK

ET #.	Tag #	Au (g/t)	Au (oz/t)
7	D96-270	1.22	0.036
22	D96-320	2.96	0.086
23	D96-321	10.48	0.306
26	D96-324	19.33	0.564
27	D96-325	18.74	0.547
28	D96-326	12.42	0.362
29	D96-327	1.15	0.034
30	D96-328	4.61	0.134
31	D96-329	1.78	0.052

XLS/96Teuton#6


ECO-TECH LABORATORIES LTD.
per Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

6-Sep-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5228

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 31
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-41
P.O.#: NONE GIVEN
Samples submitted by: DAVID HICK

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	D96-264	10	<0.2	2.05	30	55	<5	7.39	<1	25	55	51	5.10	<10	1.52	1147	5	<0.01	13	1560	<2	<5	<20	97	<0.01	<10	109	<10	2	44
2	D96-265	10	0.4	2.64	55	85	<5	9.15	<1	39	82	180	7.55	<10	2.03	1258	4	<0.01	29	1820	<2	<5	<20	144	0.02	<10	169	<10	<1	34
3	D96-266	5	<0.2	3.00	40	50	<5	5.97	<1	32	152	146	7.81	<10	3.35	1042	4	<0.01	32	2130	<2	<5	<20	100	0.08	<10	233	<10	2	48
4	D96-267	50	0.4	2.89	60	45	<5	6.21	<1	58	109	331	>10	<10	2.97	942	8	<0.01	33	1680	<2	<5	<20	102	0.02	<10	188	<10	<1	52
5	D96-268	10	0.2	2.72	20	70	<5	7.59	<1	25	93	180	6.18	<10	2.55	1220	4	<0.01	23	1960	<2	<5	<20	167	0.04	<10	158	<10	3	47
6	D96-269	60	0.4	2.74	100	70	<5	7.49	<1	30	58	125	7.31	<10	2.24	1312	5	<0.01	21	2060	<2	<5	<20	191	<0.01	<10	130	<10	<1	49
7	D96-270	>1000	0.8	2.03	40	60	<5	4.39	<1	30	38	203	6.41	<10	1.36	730	4	<0.01	11	1870	2	<5	<20	109	<0.01	<10	83	<10	<1	50
8	D96-271	770	0.4	2.28	330	90	<5	4.92	<1	23	38	83	8.11	<10	1.64	1250	7	<0.01	16	1710	<2	<5	<20	109	0.01	<10	83	<10	<1	40
9	D96-272	90	0.2	1.86	70	85	<5	7.08	<1	19	41	43	5.91	<10	1.00	1814	8	<0.01	3	1320	4	<5	<20	128	<0.01	<10	40	<10	2	24
10	D96-273	15	<0.2	1.93	20	115	<5	7.04	5	17	34	32	5.38	<10	1.16	1494	4	<0.01	8	1670	<2	<5	<20	91	<0.01	<10	38	<10	3	446
11	D96-274	10	1.0	1.72	140	90	<5	>10	<1	20	41	250	5.58	<10	1.30	2154	6	<0.01	21	1840	16	<5	<20	107	<0.01	<10	36	<10	3	95
12	D96-275	5	1.6	1.51	190	90	<5	8.07	<1	22	28	185	5.65	<10	1.16	2032	6	<0.01	23	1750	22	<5	<20	78	<0.01	<10	31	<10	2	77
13	D96-311	30	0.4	1.83	80	80	<5	>10	<1	19	30	49	6.18	<10	1.16	2599	6	<0.01	15	2420	8	<5	<20	93	<0.01	<10	48	<10	4	28
14	D96-312	5	<0.2	1.81	60	130	<5	7.77	<1	18	28	15	5.85	<10	1.08	2321	7	<0.01	9	2030	6	<5	<20	47	<0.01	<10	46	<10	3	26
15	D96-313	305	1.8	1.53	825	65	<5	8.31	<1	21	33	113	6.26	<10	0.90	2871	5	<0.01	11	1890	176	<5	<20	54	<0.01	<10	35	<10	3	49
16	D96-314	345	4.6	1.11	710	40	<5	7.23	<1	44	40	138	>10	<10	0.57	2791	11	<0.01	27	1680	554	<5	<20	46	<0.01	<10	28	<10	<1	390
17	D96-315	310	2.8	1.49	790	35	<5	3.77	<1	51	33	33	>10	<10	0.62	1747	11	<0.01	31	2590	46	<5	<20	25	<0.01	<10	45	<10	<1	60
18	D96-316	100	1.2	1.29	395	45	5	7.95	<1	35	41	61	9.25	<10	0.71	2209	8	<0.01	25	2140	22	<5	<20	53	<0.01	<10	42	<10	<1	27
19	D96-317	90	0.6	1.66	140	95	<5	>10	<1	24	40	67	8.92	<10	1.43	3624	6	<0.01	16	2040	8	<5	<20	110	<0.01	<10	54	<10	3	33
20	D96-318	15	<0.2	1.76	<5	135	5	5.90	<1	13	51	1	5.30	<10	0.97	1415	4	<0.01	3	1590	4	<5	<20	47	<0.01	<10	39	<10	<1	28
21	D96-319	5	<0.2	1.88	<5	100	5	5.66	<1	14	51	1	5.47	<10	1.02	1275	7	<0.01	4	1510	4	<5	<20	57	<0.01	<10	44	<10	2	30
22	D96-320	>1000	0.8	1.33	290	65	<5	4.32	<1	20	62	163	6.37	<10	0.69	857	6	<0.01	5	1390	10	<5	<20	42	<0.01	<10	30	<10	<1	24
23	D96-321	>1000	2.6	0.44	1840	45	<5	0.34	<1	95	62	279	>10	<10	0.10	138	20	<0.01	6	370	10	<5	<20	4	<0.01	20	11	<10	<1	18
24	D96-322	715	0.2	1.23	150	50	<5	4.73	<1	27	65	93	5.67	<10	0.64	852	5	<0.01	5	1580	4	<5	<20	43	<0.01	<10	30	<10	<1	22
25	D96-323	65	<0.2	1.98	20	95	<5	5.79	<1	19	77	47	6.34	<10	1.11	1421	7	<0.01	3	1530	2	<5	<20	75	<0.01	<10	51	<10	2	28

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
26	D96-324	>1000	5.4	0.62	2800	75	<5	1.85	<1	81	51	1498	>10	<10	0.18	1043	20	<0.01	6	120	32	<5	<20	20	<0.01	<10	14	<10	<1	33
27	D96-325	>1000	4.0	0.38	1850	45	<5	0.44	<1	103	74	658	>10	<10	0.09	190	18	<0.01	4	<10	14	<5	<20	5	<0.01	20	6	<10	<1	20
28	D96-326	>1000	2.4	0.33	2205	45	<5	2.90	<1	117	88	451	>10	<10	0.10	490	19	<0.01	7	<10	12	<5	<20	19	<0.01	<10	6	<10	<1	28
29	D96-327	>1000	0.4	1.24	520	80	<5	4.54	<1	23	91	158	>10	<10	0.70	1119	12	<0.01	3	1200	14	<5	<20	43	<0.01	<10	28	<10	<1	31
30	D96-328	>1000	1.2	0.34	1390	35	<5	4.22	<1	100	104	176	>10	<10	0.10	591	13	<0.01	8	350	8	<5	<20	32	<0.01	<10	6	<10	<1	20
31	D96-329	>1000	1.2	1.02	835	55	<5	3.26	<1	51	78	340	>10	<10	0.48	1425	19	<0.01	7	880	14	<5	<20	29	<0.01	<10	21	<10	<1	44

QC/DATA:

Resplit:

RS/1	D96-284	10	0.4	2.07	35	65	<5	>10	<1	30	60	50	5.40	<10	1.49	1220	6	<0.01	19	1610	4	<5	<20	89	<0.01	<10	115	<10	2	56
------	---------	----	-----	------	----	----	----	-----	----	----	----	----	------	-----	------	------	---	-------	----	------	---	----	-----	----	-------	-----	-----	-----	---	----


Repeat:

1	D96-264	5	<0.2	2.09	25	60	<5	8.04	<1	28	61	49	5.55	<10	1.54	1241	4	<0.01	13	1610	2	<5	<20	94	<0.01	<10	113	<10	2	53
10	D96-273	25	0.2	1.92	30	125	<5	7.14	5	19	39	30	5.46	<10	1.14	1623	5	<0.01	8	1710	2	<5	<20	85	<0.01	<10	39	<10	2	486
19	D96-317	70	0.6	1.66	125	95	<5	>10	<1	22	38	68	6.54	<10	1.42	3479	6	<0.01	14	1820	6	<5	<20	113	<0.01	<10	53	<10	3	29

Standard:

GEO'96		150	1.2	1.75	65	155	<5	2.33	<1	26	83	63	4.10	<10	0.95	869	<1	0.01	20	720	20	<5	<20	54	0.15	<10	86	<10	4	72
--------	--	-----	-----	------	----	-----	----	------	----	----	----	----	------	-----	------	-----	----	------	----	-----	----	----	-----	----	------	-----	----	-----	---	----

df/5224
XLS/96Teuton#6


ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

CERTIFICATE OF ASSAY AS 96-5228

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

09-Sep-96

ATTENTION: DINO CREMONESE

No. of samples received: 31
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-41
P.O. #: NONE GIVEN
Samples submitted by: DAVID HICK

ET #.	Tag #	Au (g/t)	Au (oz/t)
7	D96-270	1.22	0.036
22	D96-320	2.96	0.086
23	D96-321	10.48	0.306
26	D96-324	19.33	0.564
27	D96-325	18.74	0.547
28	D96-326	12.42	0.362
29	D96-327	1.15	0.034
30	D96-328	4.61	0.134
31	D96-329	1.78	0.052

XLS/96Teuton#6

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

6-Sep-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5228

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 31
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-41
P.O.#: NONE GIVEN
Samples submitted by: DAVID HICK

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	D96-264	10	<0.2	2.05	30	55	<5	7.39	<1	25	55	51	5.10	<10	1.52	1147	5	<0.01	13	1560	<2	<5	<20	97	<0.01	<10	109	<10	2	44
2	D96-265	10	0.4	2.64	55	65	<5	9.15	<1	39	82	160	7.55	<10	2.03	1258	4	<0.01	29	1620	<2	<5	<20	144	0.02	<10	189	<10	<1	34
3	D96-266	5	<0.2	3.00	40	50	<5	5.97	<1	32	152	146	7.81	<10	3.35	1042	4	<0.01	32	2130	<2	<5	<20	100	0.08	<10	233	<10	2	48
4	D96-267	50	0.4	2.89	60	45	<5	6.21	<1	58	109	331	>10	<10	2.97	942	8	<0.01	33	1680	<2	<5	<20	102	0.02	<10	186	<10	<1	52
5	D96-268	10	0.2	2.72	20	70	<5	7.59	<1	25	93	180	6.18	<10	2.55	1220	4	<0.01	23	1980	<2	<5	<20	167	0.04	<10	158	<10	3	47
6	D96-269	60	0.4	2.74	100	70	<5	7.49	<1	30	58	125	7.31	<10	2.24	1312	5	<0.01	21	2060	<2	<5	<20	191	<0.01	<10	130	<10	<1	49
7	D96-270	>1000	0.8	2.03	40	60	<5	4.39	<1	30	38	203	6.41	<10	1.36	730	4	<0.01	11	1870	2	<5	<20	109	<0.01	<10	83	<10	<1	50
8	D96-271	770	0.4	2.28	330	90	<5	4.92	<1	23	36	83	8.11	<10	1.64	1250	7	<0.01	16	1710	<2	<5	<20	109	0.01	<10	83	<10	<1	40
9	D96-272	90	0.2	1.86	70	85	<5	7.08	<1	19	41	43	5.91	<10	1.00	1614	8	<0.01	3	1320	4	<5	<20	128	<0.01	<10	40	<10	2	24
10	D96-273	15	<0.2	1.93	20	115	<5	7.04	5	17	34	32	5.38	<10	1.16	1494	4	<0.01	8	1670	<2	<5	<20	91	<0.01	<10	38	<10	3	446
11	D96-274	10	1.0	1.72	140	90	<5	>10	<1	20	41	250	5.56	<10	1.30	2154	6	<0.01	21	1840	16	<5	<20	107	<0.01	<10	36	<10	3	95
12	D96-275	5	1.6	1.51	190	90	<5	8.07	<1	22	28	185	5.65	<10	1.16	2032	6	<0.01	23	1750	22	<5	<20	78	<0.01	<10	31	<10	2	77
13	D96-311	30	0.4	1.83	80	80	<5	>10	<1	19	30	49	6.18	<10	1.16	2599	8	<0.01	15	2420	8	<5	<20	93	<0.01	<10	48	<10	4	28
14	D96-312	5	<0.2	1.81	60	130	<5	7.77	<1	18	28	15	5.85	<10	1.08	2321	7	<0.01	9	2030	6	<5	<20	47	<0.01	<10	46	<10	3	26
15	D96-313	305	1.8	1.53	825	65	<5	8.31	<1	21	33	113	6.26	<10	0.90	2871	5	<0.01	11	1890	176	<5	<20	54	<0.01	<10	35	<10	3	49
16	D96-314	345	4.6	1.11	710	40	<5	7.23	<1	44	40	138	>10	<10	0.57	2791	11	<0.01	27	1680	554	<5	<20	48	<0.01	<10	28	<10	<1	390
17	D96-315	310	2.8	1.49	790	35	<5	3.77	<1	51	33	33	>10	<10	0.62	1747	11	<0.01	31	2590	48	<5	<20	25	<0.01	<10	45	<10	<1	60
18	D96-316	100	1.2	1.29	395	45	5	7.95	<1	35	41	81	9.25	<10	0.71	2209	8	<0.01	25	2140	22	<5	<20	53	<0.01	<10	42	<10	<1	27
19	D96-317	90	0.6	1.66	140	95	<5	>10	<1	24	40	87	6.92	<10	1.43	3624	6	<0.01	16	2040	8	<5	<20	110	<0.01	<10	54	<10	3	33
20	D96-318	15	<0.2	1.76	<5	135	5	5.90	<1	13	51	1	5.30	<10	0.97	1415	4	<0.01	3	1590	4	<5	<20	47	<0.01	<10	39	<10	<1	28
21	D96-319	5	<0.2	1.88	<5	100	5	5.66	<1	14	51	1	5.47	<10	1.02	1275	7	<0.01	4	1510	4	<5	<20	57	<0.01	<10	44	<10	2	30
22	D96-320	>1000	0.8	1.33	290	65	<5	4.32	<1	20	82	163	6.37	<10	0.69	857	6	<0.01	5	1390	10	<5	<20	42	<0.01	<10	30	<10	<1	24
23	D96-321	>1000	2.6	0.44	1840	45	<5	0.34	<1	95	62	279	>10	<10	0.10	138	20	<0.01	6	370	10	<5	<20	4	<0.01	20	11	<10	<1	18
24	D96-322	715	0.2	1.23	150	50	<5	4.73	<1	27	65	93	5.67	<10	0.84	852	5	<0.01	5	1580	4	<5	<20	43	<0.01	<10	30	<10	<1	22
25	D96-323	65	<0.2	1.98	20	95	<5	5.79	<1	19	77	47	6.34	<10	1.11	1421	7	<0.01	3	1530	2	<5	<20	75	<0.01	<10	51	<10	2	28

09-09-96 16:47 0004 010 3007 ECO-TECH K.V.M.

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	D96-324	>1000	5.4	0.62	2800	75	<5	1.85	<1	81	51	1498	>10	<10	0.18	1043	20	<0.01	6	120	32	<5	<20	20	<0.01	<10	14	<10	<1	33
27	D96-325	>1000	4.0	0.38	1850	45	<5	0.44	<1	103	74	658	>10	<10	0.09	190	18	<0.01	4	<10	14	<5	<20	5	<0.01	20	6	<10	<1	20
28	D96-326	>1000	2.4	0.33	2205	45	<5	2.90	<1	117	88	451	>10	<10	0.10	490	19	<0.01	7	<10	12	<5	<20	19	<0.01	<10	6	<10	<1	28
29	D96-327	>1000	0.4	1.24	520	80	<5	4.54	<1	23	91	158	>10	<10	0.70	1119	12	<0.01	3	1200	14	<5	<20	43	<0.01	<10	28	<10	<1	31
30	D96-328	>1000	1.2	0.34	1390	35	<5	4.22	<1	100	104	176	>10	<10	0.10	591	13	<0.01	8	350	8	<5	<20	32	<0.01	<10	6	<10	<1	20
31	D96-329	>1000	1.2	1.02	835	55	<5	3.26	<1	51	78	340	>10	<10	0.46	1425	19	<0.01	7	880	14	<5	<20	29	<0.01	<10	21	<10	<1	44

QC/DATA:

Resplit:																														
RS/1	D96-264	10	0.4	2.07	35	65	<5	>10	<1	30	60	50	5.40	<10	1.49	1220	6	<0.01	19	1610	4	<5	<20	89	<0.01	<10	115	<10	2	56
Repeat:																														
1	D96-264	5	<0.2	2.09	25	60	<5	8.04	<1	28	61	49	5.55	<10	1.54	1241	4	<0.01	13	1610	2	<5	<20	94	<0.01	<10	113	<10	2	53
10	D96-273	25	0.2	1.92	30	125	<5	7.14	5	19	39	30	5.46	<10	1.14	1623	5	<0.01	8	1710	2	<5	<20	85	<0.01	<10	39	<10	2	486
19	D96-317	70	0.6	1.66	125	95	<5	>10	<1	22	38	68	6.54	<10	1.42	3479	6	<0.01	14	1820	6	<5	<20	113	<0.01	<10	53	<10	3	29
Standard:																														
GEO'96		150	1.2	1.75	65	155	<5	2.33	<1	26	83	63	4.10	<10	0.95	869	<1	0.01	20	720	20	<5	<20	54	0.15	<10	86	<10	4	72

d/5224
XLS/96Teuton#6


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5238

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

12-Sep-96

ATTENTION: DINO CREMONESE

No. of samples received: 29
Sample Type: CORE
PROJECT #: CLONE
SHIPMENT #: NONE GIVEN
P.O.#: NONE GIVEN
Samples submitted by: A. RAVEN

ET #.	Tag #	Au (g/t)	Au (oz/t)	As (%)	Co (%)
1	ERK-96 144	4.67	0.136	-	0.103
3	ERK-96 146	1.74	0.051	-	-
12	ERK-96 155	3.08	0.090	6.34	0.615
13	ERK-96 156	3.43	0.100	5.19	0.448
14	ERK-96 157	1.81	0.053	1.94	0.190
15	ERK-96 158	3.01	0.088	-	0.113
16	ERK-96 159	-	-	-	0.041
18	ERK-96 161	-	-	-	0.024
26	ERK-96 169	4.12	0.120	-	-
27	ERK-96 170	1.17	0.034	-	-

QC/DATA:


Resplit:

1	ERK-96 144	3.88	0.113	-	-
---	------------	------	-------	---	---

Standard:

SUI-a	-	-	-	0.042	-
CD-I	-	-	0.66	-	-

XLS/96Teuton#6


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5238

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 29
Sample Type: CORE
PROJECT #: CLONE
SHIPMENT #: NONE GIVEN
P.O.#: NONE GIVEN
Samples submitted by: A.RAVEN

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	ERK-96 144	>1000	0.4	3.40	6710	220	<5	1.48	<1	1016	28	472	7.76	<10	2.36	821	35	0.11	8	1690	38	<5	<20	38	0.04	<10	168	<10	<1	102
2	ERK-96 145	175	0.6	2.40	50	295	<5	1.50	1	13	35	493	4.29	<10	1.44	595	5	0.07	2	1410	34	<5	<20	42	0.03	<10	84	<10	<1	76
3	ERK-96 146	>1000	1.4	2.93	55	240	<5	2.79	<1	25	28	1192	8.27	<10	1.92	861	7	0.05	7	1130	56	<5	<20	68	0.05	<10	102	<10	<1	130
4	ERK-96 147	410	<0.2	2.93	50	390	<5	2.23	<1	18	32	434	4.83	<10	1.71	668	<1	0.10	<1	1310	38	<5	<20	77	0.12	<10	101	<10	5	82
5	ERK-96 148	110	0.8	2.64	65	305	<5	0.85	<1	30	33	1561	6.76	<10	1.78	643	53	0.06	2	1470	28	<5	<20	36	0.04	<10	111	<10	1	113
6	ERK-96 149	25	<0.2	2.98	35	210	<5	1.04	<1	18	25	139	4.85	<10	1.77	739	13	0.24	2	1810	26	<5	<20	40	0.06	<10	99	<10	3	70
7	ERK-96 150	5	<0.2	4.70	50	175	10	3.26	<1	46	38	161	9.89	<10	4.92	1536	<1	0.15	34	2080	30	<5	<20	79	0.24	<10	338	<10	2	85
8	ERK-96 151	765	<0.2	4.16	50	245	<5	2.64	<1	46	26	320	8.33	<10	3.15	1380	<1	0.14	20	1680	30	<5	<20	53	0.20	<10	226	<10	4	139
9	ERK-96 152	250	<0.2	3.57	60	205	<5	2.94	<1	39	19	203	7.28	<10	2.84	1229	<1	0.08	14	1510	20	<5	<20	52	0.17	<10	187	<10	2	141
10	ERK-96 153	10	<0.2	4.67	50	130	<5	0.73	<1	42	20	145	9.27	<10	4.80	1489	<1	0.06	30	1820	20	<5	<20	22	0.20	<10	293	<10	<1	94
11	ERK-96 154	30	<0.2	4.57	90	135	<5	1.24	2	79	15	304	8.54	<10	4.22	1542	2	0.05	20	1710	16	<5	<20	26	0.14	<10	245	<10	1	127
12	ERK-96 155	>1000	1.0	2.84	>10000	155	<5	0.24	<1	5014	12	1694	>10	<10	2.00	586	19	0.01	<1	800	58	<5	<20	16	0.04	<10	95	<10	<1	143
13	ERK-96 156	>1000	4.0	2.99	>10000	145	<5	0.17	<1	3636	20	2840	>10	<10	2.04	525	25	<0.01	<1	400	94	<5	<20	<1	0.04	<10	83	<10	<1	149
14	ERK-96 157	>1000	1.0	3.07	>10000	185	<5	0.48	<1	1864	21	1340	8.71	<10	2.57	1058	5	<0.01	<1	1060	24	<5	<20	20	0.04	<10	158	<10	<1	212
15	ERK-96 158	>1000	1.8	2.22	4875	170	<5	3.65	<1	1015	24	566	5.51	<10	1.58	1429	4	0.02	<1	1030	34	<5	<20	43	0.05	<10	105	<10	<1	129
16	ERK-96 159	575	0.6	2.75	2420	200	<5	2.51	<1	412	28	301	6.19	<10	1.86	854	7	0.07	<1	1090	30	<5	<20	47	0.05	<10	105	<10	<1	138
17	ERK-96 160	55	0.4	2.32	170	240	<5	2.11	<1	49	29	157	4.56	<10	1.48	866	<1	0.13	3	1240	30	<5	<20	52	0.05	<10	117	<10	5	104
18	ERK-96 161	515	0.8	2.03	4010	165	<5	0.89	<1	241	27	158	5.61	<10	1.39	634	2	0.05	2	1210	46	<5	<20	32	0.03	<10	101	<10	2	90
19	ERK-96 162	775	2.6	2.36	1175	145	<5	0.99	<1	83	14	901	5.11	<10	1.30	740	3	0.03	1	1410	26	<5	<20	21	0.02	<10	56	<10	1	137
20	ERK-96 163	150	0.8	2.24	200	185	<5	0.63	<1	25	11	342	4.16	<10	1.12	548	4	0.08	2	1780	20	<5	<20	16	0.03	<10	57	<10	1	100
21	ERK-96 164	225	0.8	2.27	65	155	<5	0.62	<1	24	11	258	3.67	<10	1.24	665	3	0.03	<1	1650	18	<5	<20	4	0.03	<10	45	<10	2	95
22	ERK-96 165	70	<0.2	2.58	45	160	<5	0.54	<1	20	21	128	4.22	<10	1.38	755	1	0.07	4	1310	22	<5	<20	16	0.07	<10	52	<10	3	73
23	ERK-96 166	115	2.0	2.09	700	300	<5	2.56	<1	68	20	599	3.25	<10	0.78	633	4	0.06	3	1500	14	<5	<20	57	0.03	<10	58	<10	1	58
24	ERK-96 167	70	0.8	2.10	190	240	<5	1.58	<1	24	16	182	3.40	<10	0.76	627	3	0.09	3	1620	18	<5	<20	42	0.02	<10	58	<10	3	59
25	ERK-96 168	20	1.0	2.48	50	215	<5	0.73	<1	17	26	237	4.28	<10	1.35	951	3	0.10	6	1130	20	<5	<20	29	0.09	<10	72	<10	6	89

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	ERK-96 169	>1000	9.8	3.06	2770	130	<5	0.27	<1	118	19	2958	9.26	<10	1.39	1537	6	0.03	2	760	20	<5	<20	5	0.05	<10	66	<10	<1	113
27	ERK-96 170	>1000	0.2	3.17	85	200	<5	0.47	<1	27	24	179	6.09	<10	2.26	974	<1	0.11	3	1500	18	<5	<20	28	0.13	<10	147	<10	4	107
28	ERK-96 171	80	<0.2	3.67	95	110	<5	0.54	<1	34	16	284	8.18	<10	2.88	971	2	0.12	9	2200	28	<5	<20	20	0.08	<10	197	<10	3	62
29	ERK-96 172	35	<0.2	3.68	35	130	<5	0.60	<1	32	8	186	7.88	<10	3.15	951	<1	0.08	8	2100	24	<5	<20	19	0.11	<10	192	<10	4	63

QC/DATA:

Resplit:

1	ERK-96 144	>1000	0.4	3.28	6460	195	<5	1.50	<1	930	33	456	7.68	<10	2.40	838	34	0.09	10	1760	38	<5	<20	42	0.03	<10	168	<10	1	103
---	------------	-------	-----	------	------	-----	----	------	----	-----	----	-----	------	-----	------	-----	----	------	----	------	----	----	-----	----	------	-----	-----	-----	---	-----

Repeat:

1	ERK-96 144	>1000	1.0	3.69	7090	215	<5	1.61	<1	1109	30	504	8.38	<10	2.58	886	37	0.12	8	1790	40	<5	<20	34	0.05	<10	182	<10	<1	109
10	ERK-96 153	20	<0.2	4.84	70	140	5	0.77	<1	44	21	143	9.36	<10	4.90	1507	<1	0.07	31	1800	22	<5	<20	27	0.22	<10	299	<10	1	95
19	ERK-96 162	815	2.2	2.47	1260	150	<5	1.01	<1	82	13	948	5.23	<10	1.36	756	4	0.03	1	1430	22	<5	<20	17	0.02	<10	59	<10	<1	138
28	ERK-96 171	30	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

Standard:

GEO'96		150	1.2	1.77	60	150	<5	1.88	<1	21	65	82	4.36	<10	1.01	731	<1	0.02	24	780	24	<5	<20	50	0.12	<10	79	<10	3	77
--------	--	-----	-----	------	----	-----	----	------	----	----	----	----	------	-----	------	-----	----	------	----	-----	----	----	-----	----	------	-----	----	-----	---	----

d/5238
XLS/96Teuton#6


ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5240

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

11-Sep-96

ATTENTION: DINO CREMONESE

No. of samples received: 28
Sample Type: ROCK
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
P.O.#: NONE GIVEN
Samples submitted by: NOT INDICATED


ET #.	Tag #	Au (g/t)	Au (oz/t)	As (%)	Co (%)
3	ERK-96 175	1.19	0.035	-	0.026
6	ERK-96 178	1.67	0.049	-	0.146
11	ERK-96 183	8.89	0.259	-	0.094
12	ERK-96 184	1.12	0.033	-	0.030
13	ERK-96 185	50.50	1.473	4.61	1.469
14	ERK-96 186	7.40	0.216	-	0.248
15	ERK-96 187	7.77	0.227	-	0.158
16	ERK-96 188	2.16	0.063	-	0.078
17	ERK-96 189	8.01	0.234	-	0.087
18	ERK-96 190	-	-	-	0.031
20	ERK-96 192	-	-	-	0.066
26	ERK-96 198	-	-	-	0.039

QC DATA:

Standard:

SUI-a	-	-	-	0.042
CD-I	-	-	0.66	-

XLS/96Teuton#7


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5240

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 28
Sample Type: ROCK
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
P.O.#: NONE GIVEN
Samples submitted by: NOT INDICATED

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	ERK-96 173	25	<0.2	3.63	10	140	<5	2.09	<1	34	62	130	7.56	<10	3.53	1180	<1	0.09	15	2050	16	<5	<20	40	0.19	<10	208	<10	1	43
2	ERK-96 174	5	<0.2	3.61	10	245	<5	3.74	<1	34	33	131	7.59	<10	3.75	1382	<1	0.09	12	1950	16	<5	<20	76	0.26	<10	231	<10	3	65
3	ERK-96 175	>1000	<0.2	3.89	215	355	<5	2.18	<1	215	42	290	>10	<10	3.36	1390	6	0.04	13	1940	32	<5	<20	41	0.14	<10	271	<10	<1	138
4	ERK-96 176	35	0.2	2.34	25	150	<5	0.69	<1	22	20	217	4.59	<10	1.32	674	3	0.05	4	1810	24	<5	<20	13	0.06	<10	59	<10	2	100
5	ERK-96 177	55	<0.2	2.09	30	120	<5	1.59	<1	22	17	70	3.80	<10	1.24	816	4	0.05	4	1890	26	<5	<20	24	0.04	<10	55	<10	2	73
6	ERK-96 178	>1000	<0.2	2.87	5485	120	<5	0.78	<1	1361	22	194	7.34	<10	2.13	746	20	0.02	<1	1890	22	<5	<20	15	0.03	<10	147	<10	<1	61
7	ERK-96 179	5	<0.2	4.10	160	95	<5	2.53	<1	123	41	100	8.23	<10	3.77	1417	3	0.06	15	2130	24	<5	<20	41	0.10	<10	231	<10	3	78
8	ERK-96 180	10	<0.2	4.18	95	90	<5	1.46	<1	63	28	152	8.97	<10	3.88	1249	3	0.07	13	2450	22	<5	<20	29	0.14	<10	259	<10	1	79
9	ERK-96 181	5	<0.2	3.69	20	90	<5	1.81	<1	46	51	107	7.58	<10	3.44	1298	<1	0.09	15	2020	22	<5	<20	33	0.17	<10	220	<10	3	76
10	ERK-96 182	60	<0.2	3.82	35	75	<5	0.92	<1	41	11	216	8.89	<10	3.47	1350	5	0.07	7	2300	30	<5	<20	20	0.14	<10	221	<10	2	71
11	ERK-96 183	>1000	1.8	2.86	795	280	<5	1.38	<1	938	20	1080	8.22	<10	1.65	947	6	0.02	<1	1710	20	<5	<20	27	0.03	<10	79	<10	<1	125
12	ERK-96 184	>1000	0.6	2.41	200	470	<5	2.93	<1	283	21	422	4.33	<10	1.27	953	4	0.02	2	1920	16	<5	<20	60	0.03	<10	61	<10	2	98
13	ERK-96 185	>1000	11.4	1.85	>10000	140	<5	1.26	<1	>10000	7	2038	>10	<10	1.17	796	45	<0.01	<1	630	30	<5	<20	25	0.01	<10	208	<10	<1	142
14	ERK-96 186	>1000	0.6	2.66	1475	155	<5	0.76	<1	2333	17	210	7.91	<10	1.84	1010	6	<0.01	<1	1770	22	<5	<20	10	0.02	<10	120	<10	<1	175
15	ERK-96 187	>1000	1.2	2.21	1310	415	<5	2.45	<1	1541	38	518	6.37	<10	1.39	989	5	<0.01	<1	1680	16	<5	<20	40	0.03	<10	119	<10	<1	138
16	ERK-96 188	>1000	0.4	1.91	335	235	<5	1.37	<1	864	18	381	4.36	<10	1.06	674	3	<0.01	<1	1980	14	<5	<20	18	0.02	<10	73	<10	<1	101
17	ERK-96 189	>1000	1.2	2.38	880	275	<5	0.87	<1	902	22	306	7.68	<10	1.37	699	4	<0.01	<1	2170	18	<5	<20	18	0.05	<10	102	<10	<1	202
18	ERK-96 190	470	<0.2	2.50	285	205	<5	0.58	<1	337	17	245	5.64	<10	1.53	599	3	0.01	2	2120	20	<5	<20	10	0.03	<10	70	<10	<1	143
19	ERK-96 191	65	<0.2	2.00	50	145	<5	1.27	<1	50	15	113	3.76	<10	1.09	504	2	0.07	3	1930	18	<5	<20	24	0.04	<10	53	<10	3	41
20	ERK-96 192	770	<0.2	3.78	4955	95	<5	2.67	<1	648	18	247	8.84	<10	2.95	919	12	0.04	9	1930	26	<5	<20	38	0.05	<10	169	<10	<1	78
21	ERK-96 193	60	<0.2	4.13	210	110	<5	1.93	<1	191	36	320	9.56	<10	3.62	1438	3	0.04	19	2500	24	<5	<20	27	0.11	<10	191	<10	<1	79
22	ERK-96 194	5	<0.2	3.76	25	145	<5	6.65	<1	41	33	143	8.00	<10	3.83	1611	2	0.06	15	2130	20	<5	<20	107	0.13	<10	225	<10	<1	63
23	ERK-96 195	70	<0.2	2.33	40	190	<5	2.35	<1	29	14	106	4.12	<10	1.26	833	3	0.07	3	2020	18	<5	<20	36	0.02	<10	66	<10	1	53
24	ERK-96 196	80	0.2	2.10	40	120	<5	1.51	<1	39	10	112	4.11	<10	1.33	664	4	0.07	2	2030	20	<5	<20	25	0.02	<10	74	<10	<1	64
25	ERK-96 197	175	0.4	1.98	80	135	<5	1.14	<1	71	21	155	4.21	<10	1.19	619	4	0.07	3	2040	28	<5	<20	25	0.01	<10	75	<10	<1	116

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	ERK-96 198	545	0.2	2.85	515	130	<5	1.17	<1	422	20	234	6.12	<10	2.00	703	3	0.02	5	2190	28	<5	<20	23	0.04	<10	94	<10	<1	104
27	ERK-96 199	20	<0.2	4.06	150	105	<5	2.11	<1	138	20	126	7.67	<10	3.41	1371	4	0.02	12	2500	28	<5	<20	29	0.04	<10	122	<10	5	93
28	ERK-96 200	10	<0.2	3.90	35	75	<5	3.70	<1	38	21	91	8.14	<10	3.41	1281	4	0.08	10	2190	26	<5	<20	60	0.07	<10	202	<10	3	104

QC/DATA:**Resplit:**

1	ERK-96 173	15	<0.2	3.85	15	150	<5	2.24	<1	39	70	137	7.87	<10	3.66	1220	<1	0.08	17	2120	20	<5	<20	39	0.20	<10	217	<10	<1	48
---	------------	----	------	------	----	-----	----	------	----	----	----	-----	------	-----	------	------	----	------	----	------	----	----	-----	----	------	-----	-----	-----	----	----


Repeat:

1	ERK-96 173	20	<0.2	3.83	15	140	<5	2.24	<1	37	71	139	8.15	<10	3.74	1267	<1	0.08	16	2230	20	<5	<20	40	0.20	<10	222	<10	2	48
10	ERK-96 182	80	<0.2	3.88	30	75	<5	0.93	<1	41	11	219	8.94	<10	3.49	1356	3	0.08	8	2310	30	<5	<20	18	0.15	<10	224	<10	1	72
19	ERK-96 191	15	<0.2	2.00	50	145	<5	1.28	<1	50	14	114	3.75	<10	1.10	504	2	0.06	2	1960	16	<5	<20	25	0.04	<10	52	<10	2	41

Standard:

GEO'96		150	1.0	1.88	65	145	<5	1.98	<1	21	69	72	4.04	<10	1.04	775	<1	0.02	22	710	20	<5	<20	58	0.13	<10	85	<10	5	76
--------	--	-----	-----	------	----	-----	----	------	----	----	----	----	------	-----	------	-----	----	------	----	-----	----	----	-----	----	------	-----	----	-----	---	----

dl/5240
XLS/96Teuton#6


ECO-TECH LABORATORIES LTD.
per Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

10-Sep-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5251

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 15
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-44
P.O.#: NONE GIVEN
Samples submitted by: MILO WOODWARD

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	ERK96-201	40	2.0	2.54	30	125	<5	6.54	3	26	21	81	6.50	<10	1.46	1915	10	0.01	7	1530	60	<5	<20	83	0.01	<10	74	<10	<1	194
2	ERK96-202	5	2.0	2.76	70	120	10	7.14	2	22	17	63	6.83	<10	1.87	1865	8	0.02	6	1420	74	<5	<20	95	<0.01	<10	85	<10	<1	162
3	ERK96-203	20	1.6	2.56	160	95	10	4.86	<1	20	16	52	6.33	<10	1.91	1333	7	0.01	7	1150	36	<5	<20	63	<0.01	<10	72	<10	<1	72
4	ERK96-204	5	0.6	3.77	60	105	10	5.05	<1	30	22	87	9.18	<10	3.27	1332	7	0.01	8	1250	32	<5	<20	72	0.01	<10	147	<10	<1	59
5	ERK96-205	10	0.4	3.04	85	105	10	6.44	<1	28	20	60	8.33	<10	2.58	1475	6	<0.01	6	1120	26	<5	<20	96	<0.01	<10	117	<10	<1	33
6	ERK96-206	10	0.2	3.51	45	115	15	5.64	<1	25	24	29	8.33	<10	3.11	1383	6	0.01	8	1200	26	<5	<20	80	<0.01	<10	148	<10	<1	38
7	ERK96-207	5	1.4	2.31	115	135	5	5.03	<1	26	18	95	7.83	<10	1.43	1000	13	<0.01	6	1210	42	<5	<20	82	<0.01	<10	88	<10	<1	148
8	ERK96-208	5	0.6	3.31	45	130	10	0.33	<1	33	26	68	9.93	<10	2.58	912	11	0.01	7	1360	34	<5	<20	7	<0.01	<10	149	<10	<1	84
9	ERK96-209	90	0.4	2.87	50	110	5	0.26	<1	31	25	34	>10	<10	2.42	756	12	0.02	7	1330	24	<5	<20	6	<0.01	<10	153	<10	<1	51
10	ERK96-210	20	0.4	3.00	45	110	15	2.74	<1	32	36	105	9.36	<10	2.63	827	9	0.03	8	1330	34	<5	<20	50	<0.01	<10	158	<10	<1	39
11	ERK96-211	5	0.8	3.07	35	100	<5	3.34	<1	32	54	98	>10	<10	2.80	872	8	0.02	12	1100	24	<5	<20	63	<0.01	<10	162	<10	<1	35
12	ERK96-212	5	1.0	3.12	50	100	<5	5.14	<1	18	52	125	7.20	<10	2.85	1079	7	0.02	12	1230	34	<5	<20	81	<0.01	<10	164	<10	<1	59
13	ERK96-213	5	3.0	3.48	85	100	<5	3.33	<1	42	50	238	9.91	<10	3.15	1037	9	0.01	18	1370	60	<5	<20	62	<0.01	<10	161	<10	<1	73
14	ERK96-214	10	0.4	3.10	10	1305	5	5.09	1	24	13	39	6.45	<10	1.71	1549	4	0.01	9	1190	20	<5	<20	122	0.04	<10	109	<10	<1	190
15	ERK96-215	30	0.6	2.62	30	260	10	5.28	<1	18	14	23	5.15	<10	1.23	1573	4	0.01	6	1190	38	<5	<20	117	0.02	<10	55	<10	<1	113

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
QC/DATA:																														
<i>Resplit:</i>																														
1	ERK96-201	40	1.8	2.54	25	140	<5	6.33	2	25	22	77	6.15	<10	1.40	1841	8	0.01	8	1410	56	<5	<20	87	0.01	<10	73	<10	<1	180
<i>Repeat:</i>																														
1	ERK96-201	55	1.6	2.53	30	140	10	6.02	3	24	19	76	6.03	<10	1.41	1769	9	0.01	7	1370	54	<5	<20	82	0.01	<10	73	<10	<1	173
10	ERK96-210	5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
<i>Standard:</i>																														
GEO 96		150	1.0	1.74	65	150	<5	1.80	<1	19	63	67	4.07	<10	0.97	703	<1	0.02	24	720	22	<5	<20	59	0.12	<10	78	<10	5	65

df/5242
XLS/96Teuton#6


 ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5256

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

11-Sep-96

ATTENTION: DINO CREMONESE

No. of samples received: 2
Sample Type: ROCK
PROJECT #: NONE GIVEN
SHIPMENT #: S96-45
P.O.#: NONE GIVEN
Samples submitted by: AT

ET #.	Tag #	Au (g/t)	Au (oz/t)	As (%)	Co (%)
1	ERK-96-132	6.75	0.197	1.39	0.114
2	ERK-96-133	5.93	0.173	1.42	0.102

QC/DATA:

Resplit:

RS/1 ERK-96-132	9.02	0.263	1.53	0.117
-----------------	------	-------	------	-------

Standard:

CD-1	-	-	0.66	-
SUI-a	-	-	-	0.040


ECO-TECH LABORATORIES LTD.

psr Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/96Teuton#7

6-Sep-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5256

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 2
Sample Type: ROCK
PROJECT #: NONE GIVEN
SHIPMENT #: S96-45
P.O.#: NONE GIVEN
Samples submitted by: AT

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	ERK-96-132	>1000	0.6	3.33	>10000	65	<5	4.21	<1	1177	32	226	>10	<10	2.89	1363	11	<0.01	16	2070	4	<5	<20	52	0.08	<10	210	<10	<1	68
2	ERK-96-133	>1000	0.6	3.48	>10000	65	<5	4.32	<1	1170	41	279	>10	<10	3.05	1483	13	<0.01	18	2570	18	<5	<20	45	0.07	<10	227	<10	<1	86

QC/DATA:

Resplit:

1	ERK-96-132	>1000	1.0	3.31	>10000	70	<5	4.49	<1	1226	29	239	>10	<10	2.90	1403	14	<0.01	17	2230	6	<5	<20	54	0.07	<10	210	<10	<1	70
---	------------	-------	-----	------	--------	----	----	------	----	------	----	-----	-----	-----	------	------	----	-------	----	------	---	----	-----	----	------	-----	-----	-----	----	----

Repeat:

1	ERK-96-132	>1000	1.0	3.20	>10000	65	<5	4.18	<1	1157	31	220	>10	<10	2.84	1338	11	<0.01	16	2090	4	<5	<20	50	0.07	<10	204	<10	<1	69
---	------------	-------	-----	------	--------	----	----	------	----	------	----	-----	-----	-----	------	------	----	-------	----	------	---	----	-----	----	------	-----	-----	-----	----	----

Standard:

GEO'96		30	1.2	1.72	60	150	<5	2.08	<1	24	70	62	4.11	<10	0.90	804	<1	0.01	24	710	24	<5	<20	60	0.12	<10	77	<10	4	74
--------	--	----	-----	------	----	-----	----	------	----	----	----	----	------	-----	------	-----	----	------	----	-----	----	----	-----	----	------	-----	----	-----	---	----

d/5256
XLS/96Teuton#6


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5260

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

11-Sep-96

ATTENTION: DINO CREMONESE

No. of samples received: 22

Sample Type: ROCK

PROJECT #: CLONE

SHIPMENT #: S96-45

P.O.#: NONE GIVEN

Samples submitted by: DAVID HICK


ET #.	Tag #	Au (g/t)	Au (oz/t)	As (%)	Co (%)
14	D96-343	7.76	0.226	5.53	0.458
15	D96-344	1.24	0.036	-	-
17	D96-346	1.41	0.041	-	-
18	D96-347	2.13	0.062	-	-

QC DATA:

Standard:

SUI-a - - - 0.042
CD-I - - - 0.66

XLS/96Teuton#7


ECO-TECH LABORATORIES LTD
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5260

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE


No. of samples received: 22
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-45
P.O.#: NONE GIVEN
Samples submitted by: DAVID HICK

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	D96-330	5	5.2	1.76	20	45	<5	5.02	8	31	23	203	4.81	<10	0.56	2051	5	<0.01	12	1020	88	<5	<20	64	<0.01	<10	158	<10	<1	301
2	D96-331	5	1.2	2.33	10	105	<5	4.74	5	17	19	47	5.21	<10	0.90	2606	4	<0.01	8	1150	48	<5	<20	61	<0.01	<10	96	<10	<1	249
3	D96-332	5	3.0	2.92	35	80	<5	8.18	7	19	16	47	6.97	<10	1.49	4858	7	<0.01	6	990	92	<5	<20	88	0.02	<10	87	<10	<1	418
4	D96-333	5	3.0	2.87	115	85	<5	3.82	7	22	12	67	6.98	<10	1.40	3132	8	<0.01	7	1090	98	<5	<20	53	0.01	<10	78	<10	<1	483
5	D96-334	5	2.6	2.74	135	60	<5	4.04	6	30	18	94	7.51	<10	1.47	2709	14	<0.01	11	1190	102	<5	<20	56	<0.01	<10	70	<10	<1	419
6	D96-335	10	1.4	2.00	15	50	<5	7.00	3	11	17	24	4.62	<10	0.99	4242	7	<0.01	4	1050	32	<5	<20	110	0.01	<10	44	<10	<1	175
7	D96-336	5	2.6	2.78	75	65	<5	8.41	14	20	11	42	6.96	<10	1.84	5126	16	<0.01	6	930	92	<5	<20	129	0.02	<10	56	<10	<1	612
8	D96-337	5	1.4	2.47	75	65	<5	7.51	5	17	12	59	6.14	<10	1.58	4012	8	<0.01	5	1200	20	<5	<20	96	0.01	<10	63	<10	<1	266
9	D96-338	5	0.6	2.51	360	60	<5	>10	<1	27	12	133	6.26	<10	2.02	2388	5	<0.01	8	1040	10	<5	<20	188	0.01	<10	69	<10	<1	90
10	D96-339	60	0.2	2.70	30	50	<5	7.29	<1	24	8	290	6.45	<10	1.76	1451	5	<0.01	12	1100	<2	<5	<20	155	<0.01	<10	69	<10	<1	50
11	D96-340	90	<0.2	3.05	495	60	<5	7.10	<1	53	15	213	6.93	<10	2.43	1337	2	<0.01	9	1320	4	<5	<20	122	0.01	<10	101	<10	<1	61
12	D96-341	25	<0.2	2.57	5	65	<5	8.58	1	29	19	149	6.64	<10	1.98	1569	6	<0.01	10	1690	8	<5	<20	171	<0.01	<10	88	<10	<1	92
13	D96-342	115	0.4	3.80	300	60	<5	5.55	<1	50	59	352	9.18	<10	3.47	1454	4	0.01	14	1240	<2	<5	<20	136	0.02	<10	187	<10	<1	76
14	D96-343	>1000	1.0	2.20	>10000	55	<5	6.60	<1	2877	7	265	>10	<10	1.66	1305	23	<0.01	9	550	10	<5	<20	189	<0.01	<10	78	<10	<1	43
15	D96-344	>1000	1.4	1.31	280	45	<5	6.63	<1	30	37	105	6.79	<10	0.83	1139	5	<0.01	17	750	12	<5	20	71	<0.01	<10	45	<10	<1	17
16	D96-345	80	1.8	2.20	125	55	55	4.57	<1	15	65	93	4.30	<10	1.53	1182	2	<0.01	18	1130	6	<5	<20	79	<0.01	<10	66	<10	<1	51
17	D96-346	>1000	6.0	1.59	85	45	<5	9.78	<1	12	45	1800	3.75	10	1.10	1362	2	<0.01	15	880	2	<5	<20	149	<0.01	<10	42	<10	3	42
18	D96-347	>1000	7.0	1.33	345	35	<5	>10	<1	20	45	2020	4.45	20	1.01	1630	3	<0.01	19	590	<2	<5	<20	170	<0.01	<10	38	<10	4	33
19	D96-348	80	<0.2	2.27	200	50	<5	4.81	<1	16	66	94	4.58	<10	1.68	1048	3	<0.01	17	1180	<2	<5	<20	96	<0.01	<10	75	<10	<1	23
20	D96-349	580	2.0	1.61	405	45	<5	5.11	<1	31	55	617	6.39	<10	1.07	913	5	<0.01	27	1020	14	<5	<20	77	<0.01	<10	57	<10	<1	146
21	D96-350	655	3.6	1.63	210	45	<5	7.94	<1	28	77	1203	5.42	<10	1.04	1174	5	<0.01	26	1210	2	<5	<20	126	<0.01	<10	59	<10	<1	22
22	D96-343A	170	<0.2	3.87	545	50	<5	4.59	<1	63	29	139	7.77	<10	3.92	1267	3	<0.01	9	1470	<2	<5	<20	117	0.02	<10	216	<10	<1	55

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn		
QC/DATA:																																
<i>Resplit:</i>																																
1	D96-330	5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
<i>Repeat:</i>																																
1	--D96-330	5	-5.6	1.81	15	-45	<5	5.46	9	33	25	200	5.17	<10	0.57	2222	5	<0.01	14	1070	94	<5	<20	62	<0.01	<10	170	<10	<1	338		
10	D96-339	70	<0.2	2.55	35	50	<5	7.43	<1	23	9	268	6.44	<10	1.63	1461	4	<0.01	14	1130	4	<5	<20	142	<0.01	<10	68	<10	<1	51		
19	D96-348	90	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
<i>Standard:</i>																																
GEO 96		150	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		

df/5260
XLS/96Teuton#5


 ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

11-Sep-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5261

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 10
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-47
P.O.#: NONE GIVEN
Samples submitted by: DAVID HICK

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	D96-351	60	0.6	1.90	175	40	<5	9.22	<1	20	65	141	5.06	<10	1.40	1549	4	<0.01	23	1440	<2	<5	<20	158	<0.01	<10	60	<10	<1	28
2	D96-352	35	0.8	2.62	145	45	<5	7.64	<1	21	96	95	5.82	<10	2.23	1549	4	<0.01	22	1550	12	<5	<20	122	<0.01	<10	112	<10	<1	61
3	D96-353	20	1.6	2.60	95	45	<5	6.87	<1	27	75	123	8.03	<10	2.19	1442	8	<0.01	33	1420	6	<5	<20	115	<0.01	<10	97	<10	<1	31
4	D96-354	40	0.8	2.98	770	45	<5	6.68	<1	29	80	131	7.61	<10	2.32	1530	7	<0.01	26	1550	<2	<5	<20	104	<0.01	<10	99	<10	<1	29
5	D96-355	230	0.8	2.46	2425	45	<5	6.68	<1	57	78	111	7.53	<10	2.05	1419	7	<0.01	30	1570	6	<5	<20	107	<0.01	<10	96	<10	<1	27
6	D96-356	15	0.4	2.78	215	50	<5	5.56	<1	26	89	128	7.84	<10	2.33	1471	7	<0.01	24	1680	12	<5	<20	79	<0.01	<10	101	<10	<1	31
7	D96-357	710	1.6	2.54	3380	45	<5	6.98	<1	39	80	344	>10	<10	1.95	1356	10	<0.01	30	1100	6	<5	<20	102	<0.01	<10	94	<10	<1	39
8	D96-358	990	1.6	2.56	7160	45	<5	8.15	<1	34	87	547	>10	<10	2.16	1407	10	<0.01	27	1070	<2	<5	<20	94	<0.01	<10	92	<10	<1	29
9	D96-359	450	0.6	2.78	6430	45	<5	6.00	<1	93	97	243	>10	<10	2.51	1166	9	<0.01	29	1040	6	<5	<20	77	<0.01	<10	108	<10	<1	29
10	D96-360	340	1.0	2.01	4190	45	<5	>10	<1	57	61	156	8.55	<10	1.63	1762	8	<0.01	24	940	8	<5	<20	121	<0.01	<10	65	<10	<1	22

QC/DATA:

Resplit:																															
1	D96-351	55	0.6	2.03	190	45	<5	>10	<1	23	72	149	5.20	<10	1.47	1620	5	<0.01	24	1580	2	<5	<20	152	<0.01	<10	65	<10	1	31	
Repeat:																															
1	D96-351	60	0.8	2.13	185	45	<5	>10	<1	23	75	152	5.10	<10	1.54	1620	5	<0.01	25	1460	2	<5	<20	167	<0.01	<10	68	<10	<1	34	
Standard:																															
GEO 96		150	1.2	1.91	60	150	<5	2.08	<1	21	71	76	4.06	<10	1.04	710	<1	0.02	25	780	20	<5	<20	60	0.14	<10	88	<10	4	71	

df/5216
XLS/96Teuton#7


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5273

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

13-Sep-96

ATTENTION: DINO CREMONESE


No. of samples received: 75
Sample Type: Rock
PROJECT #: Treaty Creek
SHIPMENT #: None Given
P.O.#: None Given
Samples submitted by: Alex Walus

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Zn (%)
6	A96-420	-	-	30.9	0.90	1.99	-
7	A96-421	-	-	34.1	0.99	-	-
9	A96-423	1.02	0.030	-	-	-	-
14	A96-428	1.39	0.041	-	-	-	-
33	A96-536	1.02	0.030	-	-	-	-
47	A96-555	1.07	0.031	-	-	-	-
53	A96-561	1.73	0.050	-	-	-	5.51
62	A96-570	1.63	0.048	-	-	-	-
63	A96-571	1.31	0.038	-	-	-	-
64	A96-572	1.15	0.034	-	-	-	-
71	A96-579	1.09	0.032	-	-	-	-

QC/DATA:

Standard:

Su1a	-	-	-	-	-	-	-
CPb-1	-	-	632.0	18.43	-	-	4.40
KCl _a	-	-	-	-	-	0.63	-


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/96Teuton#7

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5273

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 75
Sample Type: Rock
PROJECT #: Treaty Creek
SHIPMENT #: None Given
P.O.#: None Given
Samples submitted by: Alex Walus

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	A96-415	130	0.8	1.36	45	160	<5	0.14	<1	13	16	87	7.82	<10	0.84	1400	11	<0.01	<1	2440	42	<5	<20	16	0.03	<10	78	<10	<1	96
2	A96-416	180	3.6	0.78	160	130	<5	0.13	<1	24	34	135	5.80	<10	0.34	4132	8	<0.01	4	1790	70	<5	<20	34	<0.01	<10	42	<10	<1	101
3	A96-417	630	4.2	1.42	160	115	10	0.27	<1	14	13	17	6.84	<10	0.83	2649	7	<0.01	2	2420	76	<5	<20	16	0.01	<10	56	<10	<1	176
4	A96-418	50	2.2	1.02	105	95	<5	0.25	<1	14	17	22	6.78	<10	0.48	1490	7	<0.01	<1	2380	82	<5	<20	11	0.02	<10	52	<10	<1	103
5	A96-419	730	19.8	0.94	205	120	<5	0.14	<1	22	34	688	6.53	<10	0.29	5514	24	<0.01	3	1890	68	<5	<20	7	0.04	<10	34	<10	<1	78
6	A96-420	255	>30	1.66	50	80	<5	2.90	2	25	26	>10000	6.41	<10	0.85	8572	9	0.03	6	1750	30	<5	<20	30	0.10	<10	134	<10	5	335
7	A96-421	535	>30	0.46	810	90	<5	0.13	<1	9	38	970	4.18	<10	0.02	503	19	<0.01	<1	1560	68	105	<20	7	0.10	<10	21	<10	<1	89
8	A96-422	630	28.8	0.63	540	55	<5	0.27	<1	17	24	1761	6.68	<10	0.12	1271	61	<0.01	1	2670	48	<5	<20	8	0.09	<10	39	<10	<1	113
9	A96-423	>1000	13.2	1.57	40	240	<5	0.53	1	21	19	7414	3.39	<10	1.07	4487	17	0.04	4	2470	44	<5	<20	12	0.02	<10	85	<10	8	397
10	A96-424	30	2.4	0.66	115	60	<5	0.25	<1	13	20	187	6.36	<10	0.23	887	26	<0.01	1	2090	54	<5	<20	5	<0.01	<10	36	<10	<1	82
11	A96-425	155	0.6	3.24	35	375	<5	0.98	1	33	21	265	7.27	<10	2.23	5662	7	0.02	6	2420	46	<5	<20	24	0.14	<10	112	<10	6	248
12	A96-426	245	0.8	1.54	115	75	<5	0.40	<1	21	30	222	8.28	<10	1.06	2975	8	<0.01	2	2540	58	<5	<20	14	0.15	<10	109	<10	<1	152
13	A96-427	45	0.6	1.63	85	120	<5	0.50	<1	23	25	98	9.35	<10	1.35	2604	2	0.01	2	2640	62	<5	<20	17	0.24	<10	191	<10	<1	130
14	A96-428	>1000	10.8	1.71	255	50	<5	0.43	<1	78	32	493	9.05	<10	0.76	6439	21	<0.01	7	3320	138	<5	<20	8	0.06	<10	66	<10	1	176
15	A96-518	80	0.4	0.85	135	50	10	0.21	<1	13	35	10	6.29	<10	0.61	667	6	0.01	<1	1780	32	<5	<20	52	0.03	<10	62	<10	<1	41
16	A96-519	135	0.4	1.46	170	75	10	0.28	<1	14	31	17	6.68	<10	1.17	1034	6	0.02	1	2400	32	<5	<20	24	<0.01	<10	84	<10	<1	54
17	A96-520	105	0.4	0.89	210	55	10	0.19	<1	13	25	10	6.83	<10	0.58	737	11	<0.01	2	2100	40	<5	<20	23	<0.01	<10	49	<10	<1	44
18	A96-521	25	0.4	0.98	255	280	10	0.04	<1	7	50	8	7.78	<10	0.69	1073	8	0.01	2	2270	28	<5	<20	19	<0.01	<10	66	<10	<1	45
19	A96-522	110	0.8	0.84	675	115	10	0.89	<1	13	28	5	7.06	<10	0.43	2329	6	<0.01	1	1940	24	<5	<20	8	<0.01	<10	58	<10	<1	68
20	A96-523	120	0.6	0.50	550	60	10	1.01	<1	17	67	4	5.89	<10	0.09	1650	5	<0.01	4	1990	76	<5	<20	19	<0.01	<10	34	<10	<1	124
21	A96-524	110	1.0	1.11	515	65	10	0.25	<1	14	25	8	6.28	<10	0.75	1682	6	<0.01	2	1990	56	<5	<20	36	<0.01	<10	66	<10	<1	101
22	A96-525	30	0.4	1.03	200	55	<5	0.41	<1	15	76	2	6.21	<10	0.76	1512	6	0.01	4	1960	20	<5	<20	18	<0.01	<10	71	<10	<1	82
23	A96-526	75	0.2	0.81	155	50	15	0.20	<1	14	23	2	6.43	<10	0.61	1207	7	<0.01	3	1970	18	<5	<20	21	<0.01	<10	55	<10	<1	78
24	A96-527	5	0.4	0.92	50	55	5	0.22	<1	11	69	<1	5.51	<10	0.80	1252	4	0.01	2	1640	14	<5	<20	15	<0.01	<10	68	<10	<1	57
25	A96-528	90	<0.2	0.58	245	75	15	0.13	<1	11	31	2	6.08	<10	0.32	721	6	0.01	2	1940	16	<5	<20	42	<0.01	<10	42	<10	<1	36

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
26	A96-529	155	<0.2	0.91	800	50	5	1.04	<1	16	58	1	6.49	<10	0.78	1554	5	0.01	3	1990	20	<5	<20	21	<0.01	<10	77	<10	<1	61
27	A96-530	10	0.4	0.74	215	35	5	0.61	<1	12	21	<1	5.76	<10	0.64	1277	6	<0.01	2	1740	14	<5	<20	49	<0.01	<10	49	<10	<1	59
28	A96-531	255	0.6	0.56	305	45	5	0.34	<1	9	75	2	4.74	<10	0.20	838	3	<0.01	2	1390	20	<5	<20	70	<0.01	<10	38	<10	<1	70
29	A96-532	50	1.0	0.29	335	65	<5	0.83	<1	17	39	84	5.26	<10	0.13	935	7	<0.01	5	2320	8	<5	<20	17	<0.01	<10	54	<10	<1	29
30	A96-533	230	2.2	0.26	540	65	<5	0.64	<1	10	106	99	5.29	<10	0.05	600	4	<0.01	3	1570	16	10	<20	25	<0.01	<10	47	<10	<1	30
31	A96-534	310	5.6	0.41	930	40	<5	0.99	<1	18	38	406	7.08	<10	0.25	1053	8	<0.01	3	2650	20	20	<20	12	<0.01	<10	52	<10	<1	96
32	A96-535	475	6.2	0.49	1025	50	<5	0.95	<1	19	70	360	8.28	<10	0.28	1035	7	<0.01	3	2340	20	15	<20	15	<0.01	<10	62	<10	<1	69
33	A96-536	>1000	22.0	2.24	1525	50	<5	4.99	<1	54	19	1694	>10	<10	2.33	7816	29	<0.01	5	1070	76	5	<20	48	0.02	<10	218	<10	<1	722
34	A96-542	25	0.6	1.07	160	85	5	0.24	<1	12	19	28	5.24	<10	0.68	1178	3	<0.01	2	1990	32	<5	<20	7	0.10	<10	62	<10	<1	76
35	A96-543	540	1.0	0.29	125	105	5	0.06	<1	4	15	14	3.35	<10	0.04	115	6	<0.01	<1	1450	40	<5	<20	16	0.02	<10	12	<10	<1	13
36	A96-544	105	0.6	0.28	95	140	5	0.05	<1	4	9	11	2.94	<10	0.04	153	6	<0.01	<1	1350	48	<5	<20	11	0.03	<10	10	<10	<1	21
37	A96-545	130	0.4	0.24	70	215	<5	0.04	<1	2	16	3	1.64	<10	0.02	46	2	<0.01	<1	920	28	<5	<20	12	0.03	<10	6	<10	<1	6
38	A96-546	80	0.4	0.78	50	210	10	0.17	<1	5	12	10	3.75	<10	0.40	674	4	<0.01	<1	1980	34	<5	<20	17	0.04	<10	33	<10	2	65
39	A96-547	130	0.4	0.37	60	55	<5	0.05	<1	5	36	10	3.58	<10	0.06	142	6	<0.01	1	1210	44	<5	<20	38	<0.01	<10	9	<10	<1	24
40	A96-548	125	0.6	0.68	65	150	<5	0.09	<1	9	33	16	3.34	<10	0.37	596	7	<0.01	15	1260	56	<5	<20	15	0.01	<10	21	<10	<1	66
41	A96-549	375	0.4	0.27	50	95	<5	0.02	<1	2	64	3	2.02	<10	0.02	47	4	<0.01	1	640	68	<5	<20	28	<0.01	<10	5	<10	<1	28
42	A96-550	410	1.0	0.23	60	225	<5	0.02	<1	1	21	2	1.96	<10	0.02	42	5	<0.01	<1	660	70	<5	<20	18	<0.01	<10	6	<10	<1	21
43	A96-551	250	0.2	0.32	45	60	5	0.07	<1	4	30	2	3.01	<10	0.06	111	5	<0.01	2	1180	110	<5	<20	18	0.02	<10	10	<10	<1	27
44	A96-552	335	0.4	0.21	25	35	<5	0.03	<1	5	20	1	2.26	<10	<0.01	23	8	<0.01	<1	660	50	<5	<20	19	<0.01	<10	5	<10	<1	13
45	A96-553	175	0.4	0.31	35	35	10	0.03	<1	5	51	3	2.96	<10	0.02	36	6	<0.01	2	690	60	<5	<20	19	<0.01	<10	7	<10	<1	19
46	A96-554	560	0.4	0.80	90	130	<5	0.26	<1	6	19	10	3.75	<10	0.42	619	4	<0.01	2	2230	76	<5	<20	10	0.07	<10	36	<10	<1	72
47	A96-555	>1000	0.4	0.60	60	115	<5	0.18	<1	3	70	3	2.43	<10	0.22	281	1	<0.01	2	1720	36	<5	<20	14	0.03	<10	21	<10	<1	20
48	A96-556	680	0.6	0.26	35	55	<5	0.12	<1	5	36	3	2.27	<10	0.02	82	4	<0.01	2	1550	58	<5	<20	12	0.01	<10	10	10	<1	8
49	A96-557	5	0.2	1.03	165	65	<5	0.28	<1	7	26	6	4.78	<10	0.75	1240	3	0.01	2	2090	58	<5	<20	9	0.04	<10	71	<10	<1	102
50	A96-558	475	0.6	0.86	75	55	<5	0.40	<1	8	17	13	4.22	<10	0.53	1175	2	<0.01	<1	1990	54	<5	<20	8	0.07	<10	47	<10	<1	85
51	A96-559	25	0.2	1.30	40	50	10	0.48	<1	12	30	6	5.11	<10	0.97	2145	3	0.02	3	2260	60	<5	<20	7	0.04	<10	73	<10	<1	140
52	A96-560	15	0.6	1.25	70	105	<5	0.25	<1	6	14	15	5.57	<10	0.91	1892	4	0.01	<1	2420	62	<5	<20	23	0.03	<10	77	<10	<1	152
53	A96-561	>1000	<0.2	0.42	135	30	<5	0.73	725	6	54	63	2.30	<10	0.24	298	<1	<0.01	2	710	3148	<5	<20	91	<0.01	<10	19	<10	<1	>10000
54	A96-562	390	6.8	2.38	95	190	<5	>10	16	19	23	408	1.81	80	0.98	>10000	2	<0.01	193	340	62	<5	<20	121	0.03	<10	12	<10	46	597
55	A96-563	5	0.2	1.04	170	40	15	1.10	<1	23	53	29	6.07	<10	0.80	1914	4	0.01	9	2290	58	<5	<20	23	<0.01	<10	63	<10	5	226
56	A96-564	705	2.4	0.75	260	40	<5	1.18	<1	16	46	224	8.03	<10	0.24	1591	10	<0.01	14	1060	72	<5	<20	16	<0.01	<10	31	<10	3	218
57	A96-565	915	1.0	0.28	125	40	10	0.79	<1	13	97	31	4.74	<10	0.03	1336	6	<0.01	11	570	24	<5	<20	19	<0.01	<10	21	<10	<1	63
58	A96-566	475	0.8	0.20	75	40	<5	0.05	<1	6	110	9	3.18	<10	<0.01	105	11	<0.01	8	370	22	<5	<20	8	<0.01	<10	13	<10	<1	25
59	A96-567	310	0.8	0.21	25	35	<5	0.17	<1	8	105	11	3.76	<10	<0.01	108	4	<0.01	8	410	12	<5	<20	9	<0.01	<10	7	<10	<1	25
60	A96-568	650	2.0	0.25	120	30	<5	0.50	<1	13	84	174	9.58	<10	<0.01	171	14	<0.01	10	520	44	<5	<20	7	<0.01	<10	8	<10	<1	26

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
61	A96-569	605	1.6	0.19	130	35	10	0.20	<1	14	84	13	9.96	<10	<0.01	103	13	<0.01	10	220	28	<5	<20	9	<0.01	<10	8	<10	<1	51
62	A96-570	>1000	2.4	0.22	325	50	35	0.40	<1	28	64	13	>10	<10	<0.01	532	27	<0.01	10	260	44	<5	<20	9	<0.01	<10	8	<10	<1	83
63	A96-571	>1000	2.8	0.18	275	45	20	0.46	<1	16	160	16	>10	<10	0.02	673	19	<0.01	8	110	54	<5	<20	6	<0.01	<10	10	<10	<1	72
64	A96-572	>1000	2.8	0.26	175	45	15	0.24	<1	19	58	23	>10	<10	<0.01	282	19	<0.01	12	280	50	<5	<20	7	<0.01	<10	7	<10	<1	47
65	A96-573	745	1.6	0.28	205	35	20	0.26	<1	28	75	33	>10	<10	<0.01	128	12	<0.01	20	900	26	<5	<20	6	<0.01	<10	6	<10	<1	52
66	A96-574	720	1.2	0.31	140	20	<5	1.23	<1	8	41	8	4.29	<10	0.19	1317	6	<0.01	12	610	48	<5	<20	13	<0.01	<10	9	<10	<1	163
67	A96-575	325	1.2	1.03	75	40	5	1.08	<1	15	121	29	4.39	<10	0.97	1069	5	<0.01	31	750	32	<5	<20	14	<0.01	<10	39	<10	2	78
68	A96-576	525	1.2	0.40	160	30	10	0.44	<1	13	42	46	7.09	<10	0.08	507	9	<0.01	14	780	26	<5	<20	9	<0.01	<10	9	<10	<1	66
69	A96-577	725	1.6	0.30	140	45	5	0.69	<1	13	45	40	5.53	<10	0.08	601	9	<0.01	10	680	18	<5	<20	12	<0.01	<10	44	<10	<1	40
70	A96-578	170	1.4	0.20	110	25	<5	0.05	<1	11	46	31	4.62	<10	<0.01	72	8	<0.01	11	260	26	<5	<20	7	<0.01	<10	6	<10	<1	21
71	A96-579	>1000	3.2	0.28	210	45	35	0.81	<1	21	82	31	>10	<10	0.04	898	17	<0.01	7	330	48	<5	<20	11	<0.01	<10	14	<10	<1	58
72	A96-580	580	1.6	0.21	70	30	5	1.57	<1	10	58	20	3.65	<10	0.09	1866	8	<0.01	17	930	10	<5	<20	18	<0.01	<10	36	10	2	43
73	A96-581	515	1.2	0.24	80	20	<5	2.18	<1	7	105	21	3.07	<10	0.08	1933	4	<0.01	8	380	34	<5	<20	29	<0.01	<10	9	<10	1	96
74	A96-582	425	0.8	0.27	85	25	5	0.56	<1	11	35	24	4.84	<10	0.10	702	7	<0.01	11	680	58	<5	<20	8	<0.01	<10	7	<10	<1	110
75	A96-583	60	0.4	0.08	365	40	<5	0.01	<1	12	66	14	>10	<10	<0.01	16	13	<0.01	3	<10	12	<5	<20	6	<0.01	<10	2	<10	<1	4

QC/DATA:

Resplit:

RS/1	A96-415	125	0.6	1.07	45	140	<5	0.11	<1	10	13	78	7.49	<10	0.63	1304	8	<0.01	<1	2290	40	<5	<20	12	0.02	<10	61	<10	<1	85
RS/36	A96-544	100	0.6	0.36	105	135	5	0.06	<1	4	12	12	3.38	<10	0.05	165	6	<0.01	<1	1420	52	<5	<20	13	0.03	<10	12	<10	<1	25

Repeat:

1	A96-415	130	0.8	1.29	40	165	<5	0.14	<1	12	15	84	7.84	<10	0.80	1395	11	<0.01	<1	2430	40	<5	<20	14	0.03	<10	76	<10	<1	95
10	A96-424	50	2.4	0.64	120	55	<5	0.25	<1	13	21	182	6.49	<10	0.22	897	25	<0.01	1	2160	54	<5	<20	5	<0.01	<10	36	<10	<1	87
19	A96-522	110	0.8	0.88	645	100	10	0.89	<1	13	27	5	7.06	<10	0.45	2360	7	<0.01	3	1900	20	<5	<20	8	<0.01	<10	59	<10	<1	65
36	A96-544	95	0.6	0.30	105	155	5	0.05	<1	4	10	11	3.04	<10	0.04	159	5	<0.01	<1	1390	50	<5	<20	15	0.03	<10	10	<10	<1	23
45	A96-553	185	0.4	0.33	45	40	<5	0.03	<1	5	54	3	3.05	<10	0.03	37	7	<0.01	3	700	62	<5	<20	19	<0.01	<10	7	<10	<1	24
54	A96-562	365	6.6	2.28	80	200	<5	>10	17	20	25	387	1.87	70	0.95	>10000	3	<0.01	200	370	72	5	<20	112	0.03	<10	12	<10	45	639
71	A96-579	-	2.6	0.23	190	45	30	0.67	<1	17	76	28	>10	<10	0.03	828	13	<0.01	7	240	42	<5	<20	10	<0.01	<10	11	<10	<1	47

Standard:

GEO'96		150	1.4	1.72	65	115	<5	1.72	<1	15	62	74	3.82	<10	0.97	680	1	<0.01	20	630	24	<5	<20	58	0.08	<10	76	<10	<1	68
GEO'96		150	1.2	1.61	70	150	<5	1.97	<1	21	67	71	4.01	<10	0.89	756	1	0.01	24	710	24	<5	<20	55	0.11	<10	78	<10	4	74
GEO'96		150	1.0	1.61	60	130	<5	1.73	<1	19	59	70	4.00	<10	0.92	658	1	<0.01	24	780	24	<5	<20	56	0.10	<10	74	<10	3	69

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5278

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 14

Sample Type: ROCK

PROJECT #: CLONE

SHIPMENT #: NONE GIVEN

P.O. #: S96-48

Samples submitted by: DAVID HICK

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	D96-361	5	0.8	1.72	<5	245	<5	3.17	<1	12	30	11	3.54	<10	0.85	1108	3	<0.01	3	1170	22	<5	<20	61	<0.01	<10	21	<10	<1	198
2	D96-362	5	0.4	1.31	<5	1515	10	3.54	<1	7	24	<1	4.50	<10	0.58	1133	4	<0.01	3	1110	16	<5	<20	140	0.03	<10	24	<10	<1	160
3	D96-363	5	0.8	0.81	10	1330	<5	4.92	<1	8	15	3	3.73	<10	0.36	1526	3	<0.01	2	1060	18	5	<20	114	0.03	<10	22	<10	<1	117
4	D96-364	5	<0.2	1.02	15	1485	10	3.40	<1	9	24	1	4.20	<10	0.56	1081	3	<0.01	3	1260	18	<5	<20	135	0.02	<10	17	<10	<1	205
5	D96-365	5	0.8	1.96	<5	380	<5	3.56	1	14	23	8	4.23	<10	0.91	1268	5	<0.01	4	1180	16	5	<20	79	0.01	<10	23	<10	<1	123
6	D96-366	5	2.2	1.33	25	175	<5	5.28	2	13	29	15	3.08	<10	0.70	1442	4	<0.01	2	960	130	<5	<20	66	<0.01	<10	18	<10	<1	182
7	D96-367	10	0.8	2.04	45	160	5	1.05	<1	23	15	25	5.74	<10	0.90	628	6	<0.01	7	1850	26	<5	<20	20	<0.01	<10	48	<10	<1	105
8	D96-368	40	0.6	2.29	35	170	5	0.52	<1	17	27	42	7.19	<10	0.65	475	7	<0.01	4	1450	28	<5	<20	11	0.01	<10	51	<10	<1	70
9	D96-369	5	0.8	2.53	40	225	<5	2.68	<1	18	22	20	5.41	<10	1.26	1174	6	<0.01	9	1120	32	<5	<20	54	0.01	<10	55	<10	<1	115
10	D96-370	5	0.8	2.94	80	150	<5	4.70	<1	23	11	80	6.59	<10	2.08	1304	7	0.01	6	1250	30	<5	<20	59	<0.01	<10	99	<10	<1	62
11	D96-371	5	0.6	2.30	65	115	<5	5.03	<1	21	12	88	7.01	<10	1.65	1103	7	<0.01	5	1120	20	<5	<20	70	<0.01	<10	88	<10	<1	35
12	D96-372	15	1.0	2.86	105	135	10	3.28	<1	31	29	85	8.36	<10	2.04	1050	7	<0.01	7	1240	46	<5	<20	43	0.01	<10	111	<10	<1	88
13	D96-373	45	2.0	1.71	95	115	<5	3.56	5	43	23	141	>10	<10	0.91	1100	30	<0.01	13	1000	82	<5	<20	43	<0.01	<10	67	<10	<1	244
14	D96-374	5	1.6	2.66	35	120	<5	3.54	3	34	42	134	7.30	<10	1.74	1138	9	<0.01	13	1620	54	<5	<20	45	<0.01	<10	134	<10	<1	228
QC/DATA:																														
Resplit:																														
1	D96-361	5	0.8	1.79	<5	255	10	3.40	<1	15	25	13	3.63	<10	0.92	1221	4	<0.01	4	1240	28	<5	<20	64	<0.01	<10	21	<10	<1	212
Repeat:																														
1	D96-361	5	0.8	1.63	<5	230	<5	3.06	<1	11	31	10	3.41	<10	0.81	1069	2	<0.01	<1	1110	20	<5	<20	61	<0.01	<10	19	<10	<1	189
Standard:																														
GEO 96		140	1.4	1.65	60	150	<5	1.87	<1	20	64	69	4.34	<10	0.92	739	<1	0.01	24	790	24	<5	<20	55	0.13	<10	77	<10	3	68

per
ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5279

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

17-Sep-96

ATTENTION: DINO CREMONESE

*No. of samples received: 32
Sample Type: Rock
PROJECT #: Clone
SHIPMENT #: S96-49
P.O.#: None Given
Samples submitted by: A. Raven*

ET #.	Tag #	Au (g/t)	Au (oz/t)	As (%)	Co (%)	Zn (%)
2	ERK-96-217	-	-	-	-	1.79
4	ERK-96-219	2.09	0.061	1.44	0.057	-
7	ERK-96-222	-	-	-	-	1.38
22	ERK-96-237	8.76	0.255	-	0.027	-

QC/DATA:

Standard:

CD-1	-	-	0.66	-	-
Su-1a	-	-	-	0.042	-
CPb-1	-	-	-	-	4.40

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/96Teuton#7

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5279

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 32

Sample Type: Rock -

PROJECT #: Clone

SHIPMENT #: S96-49

P.O.#: None Given

Samples submitted by: A. Raven

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	ERK-96-216	80	5.2	1.86	320	155	<5	>10	8	24	27	69	6.18	<10	0.74	3700	6	<0.01	14	1200	476	<5	<20	164	0.01	<10	55	<10	<1	829
2	ERK-96-217	25	9.8	2.24	105	125	<5	5.95	157	23	24	150	7.21	<10	0.89	3536	<1	<0.01	6	1910	70	<5	<20	78	0.01	<10	58	<10	<1	>10000
3	ERK-96-218	50	5.6	3.03	260	170	<5	3.30	37	31	20	144	8.49	<10	1.24	2697	13	<0.01	11	2830	176	<5	<20	47	0.01	<10	81	<10	<1	2999
4	ERK-96-219	>1000	11.6	1.55	>10000	105	<5	0.85	<1	827	64	207	8.34	<10	0.47	901	9	<0.01	5	1240	46	10	<20	16	<0.01	<10	39	<10	<1	2211
5	ERK-96-220	20	2.8	1.27	180	80	<5	0.50	<1	30	23	26	5.95	<10	0.41	191	10	<0.01	8	2440	30	<5	<20	8	<0.01	<10	38	<10	<1	81
6	ERK-96-221	15	4.4	2.20	165	175	<5	0.49	<1	33	42	131	8.94	<10	0.76	349	13	<0.01	11	2160	32	<5	<20	5	<0.01	20	72	<10	<1	107
7	ERK-96-222	130	5.4	2.58	345	210	<5	2.58	184	36	29	370	9.78	<10	1.13	1707	5	0.01	13	2690	246	<5	<20	42	0.01	<10	73	<10	<1	>10000
8	ERK-96-223	5	3.4	4.11	105	105	<5	3.84	<1	30	47	221	9.63	<10	3.84	1834	8	<0.01	7	1640	64	<5	<20	63	<0.01	<10	182	<10	<1	142
9	ERK-96-224	10	4.6	4.09	100	160	<5	4.51	8	35	74	175	>10	<10	3.43	1895	18	<0.01	16	1750	218	<5	<20	102	<0.01	<10	168	<10	<1	541
10	ERK-96-225	5	2.8	2.32	40	220	<5	2.44	<1	27	37	72	6.49	<10	1.35	765	9	<0.01	6	1140	28	<5	<20	56	<0.01	<10	53	<10	<1	74
11	ERK-96-226	5	1.0	3.59	<5	605	5	3.66	3	43	27	232	8.85	<10	2.43	1625	9	<0.01	13	1470	36	<5	<20	106	0.03	<10	132	<10	<1	434
12	ERK-96-227	20	2.4	3.33	90	350	<5	2.39	6	27	47	78	7.36	<10	1.84	2904	4	<0.01	8	1410	92	<5	<20	33	0.02	<10	85	<10	<1	824
13	ERK-96-228	5	2.0	1.72	105	150	<5	7.07	43	19	15	65	4.14	<10	0.62	2048	4	<0.01	8	1370	22	<5	<20	77	0.01	<10	36	<10	3	2749
14	ERK-96-229	10	3.2	2.12	280	275	<5	1.10	8	38	29	84	6.55	<10	0.80	1295	7	<0.01	9	2010	30	<5	<20	18	0.01	<10	55	<10	<1	1037
15	ERK-96-230	5	3.0	1.89	135	130	10	0.44	3	28	29	65	7.31	<10	0.61	632	12	<0.01	7	2170	30	<5	<20	7	<0.01	<10	55	<10	<1	673
16	ERK-96-231	10	2.6	1.52	145	115	<5	0.77	16	34	56	46	6.19	<10	0.43	894	12	<0.01	9	2070	28	<5	<20	9	<0.01	<10	41	<10	<1	995
17	ERK-96-232	5	1.8	2.07	100	165	<5	3.31	2	23	33	25	6.63	<10	0.71	2490	12	<0.01	8	1610	14	<5	<20	36	0.01	<10	50	<10	<1	438
18	ERK-96-233	5	1.6	2.93	70	215	5	2.19	2	32	38	110	8.51	<10	1.03	1748	21	0.01	15	2640	24	<5	<20	27	0.01	<10	77	<10	<1	135
19	ERK-96-234	5	0.2	1.69	65	100	5	3.66	<1	22	27	82	4.70	<10	1.32	881	7	0.02	6	1500	22	<5	<20	54	<0.01	<10	51	<10	<1	50
20	ERK-96-235	5	<0.2	2.16	130	105	<5	1.78	<1	23	31	101	5.99	<10	1.66	920	7	0.03	5	1290	22	<5	<20	37	0.01	<10	73	<10	<1	56
21	ERK-96-236	50	0.4	1.95	105	100	<5	2.88	<1	23	23	98	5.73	<10	1.36	935	6	0.03	6	1270	30	<5	<20	51	<0.01	<10	71	<10	<1	80
22	ERK-96-237	>1000	2.6	2.39	7615	100	<5	3.15	<1	411	28	287	8.91	<10	1.26	1040	34	0.01	13	1720	48	<5	<20	56	0.01	<10	84	<10	<1	279
23	ERK-96-238	30	<0.2	2.36	35	95	10	4.72	1	20	42	16	4.86	<10	2.08	1203	4	0.04	10	1990	22	<5	<20	92	0.02	<10	161	<10	<1	110
24	ERK-96-239	10	<0.2	2.51	20	85	<5	4.56	<1	19	50	8	5.06	<10	2.25	1126	2	0.06	8	1910	16	<5	<20	82	0.03	<10	165	<10	<1	80
25	ERK-96-333 Aw	80	2.4	3.77	190	115	15	0.46	<1	35	39	162	>10	<10	2.79	862	19	0.02	9	1630	42	<5	<20	6	<0.01	<10	143	<10	<1	67

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	ERK-96-334	65	2.0	3.57	145	100	<5	2.21	<1	36	69	87	>10	<10	3.01	1228	10	0.01	8	1640	38	<5	<20	36	<0.01	<10	162	<10	<1	63
27	ERK-96-335	25	1.6	2.98	135	95	<5	2.56	<1	27	41	119	8.21	<10	2.41	1057	10	0.02	7	1660	32	<5	<20	39	<0.01	<10	126	<10	<1	68
28	ERK-96-336	5	1.0	2.41	40	110	<5	4.28	4	27	44	47	6.33	<10	1.55	1368	13	<0.01	11	1330	40	<5	<20	74	<0.01	<10	70	<10	<1	207
29	ERK-96-337	5	0.8	1.74	20	155	<5	1.23	1	14	26	8	4.23	<10	0.99	704	4	<0.01	3	1300	48	<5	<20	33	<0.01	<10	22	<10	<1	366
30	ERK-96-338	5	2.0	2.49	10	250	10	3.66	8	16	38	21	5.30	<10	1.25	1389	5	<0.01	4	1340	92	<5	<20	52	0.01	<10	37	<10	<1	505
31	ERK-96-339	5	3.6	1.78	45	135	5	3.28	2	14	27	14	5.00	<10	0.89	1201	8	<0.01	4	1170	70	10	<20	50	<0.01	<10	28	<10	<1	424
32	ERK-96-340	5	1.4	3.08	75	105	<5	0.58	<1	38	37	176	9.61	<10	2.31	1295	10	<0.01	8	1480	68	<5	<20	9	<0.01	<10	127	<10	<1	122

QC/DATA:

Resplit:

1	ERK-96-216	75	5.2	1.73	290	140	<5	>10	8	21	18	65	6.28	<10	0.67	3486	5	<0.01	10	1090	444	<5	<20	154	0.01	<10	46	<10	<1	737
---	------------	----	-----	------	-----	-----	----	-----	---	----	----	----	------	-----	------	------	---	-------	----	------	-----	----	-----	-----	------	-----	----	-----	----	-----

Repeat:


1	ERK-96-216	65	5.8	2.00	335	155	5	>10	9	24	28	73	6.34	<10	0.79	3813	8	<0.01	16	1240	482	<5	<20	177	0.01	<10	59	<10	<1	823
10	ERK-96-225	5	2.6	2.39	40	225	<5	2.60	<1	29	42	74	6.87	<10	1.38	810	14	<0.01	9	1280	30	5	<20	58	<0.01	<10	56	<10	<1	81
19	ERK-96-234	5	0.2	1.87	75	110	<5	3.69	1	22	29	84	4.87	<10	1.41	898	8	0.02	7	1470	20	<5	<20	55	<0.01	<10	56	<10	<1	50
31	ERK-96-349	5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

Standard:

GEO'96		150	1.4	1.63	55	150	<5	1.74	<1	18	63	72	3.93	<10	0.92	694	3	0.01	24	730	20	10	<20	55	0.10	<10	73	<10	4	67
GEO'96		150	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

df/5278
XLS/96Teuton#7


ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer



ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5286

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

17-Sep-96

ATTENTION: DINO CREMONESE

No. of samples received: 20
Sample Type: ROCK
PROJECT #: NOT GIVEN
SHIPMENT #: 596-50
P.O.#: CLONE
Samples submitted by: A.L.

ET #.	Tag #	Au (g/t)	Au (oz/t)	Co %
1	A96 - 370	2.12	0.062	-
18	A96 - 387	20.33	0.593	0.033

QC/DATA:

Resplit:

1	A96 - 370	1.97	0.057	-
---	-----------	------	-------	---

Standard:

Su1a	-	-	0.040
------	---	---	-------


ECO-TECH LABORATORIES LTD.

per Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/96Teuton#7

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5286

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE


No. of samples received:20
Sample Type:ROCK
PROJECT #:NOT GIVEN
SHIPMENT #:596-50
P.O.#: CLONE
Samples submitted by:A.L.

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	A96 - 370	>1000	<0.2	3.21	150	60	<5	3.53	<1	57	32	322	8.35	<10	2.79	992	8	0.02	11	1380	<2	<5	<20	50	0.07	<10	222	<10	<1	57
2	A96 - 371	15	<0.2	3.58	40	65	<5	5.44	<1	36	29	135	8.04	<10	3.53	1271	2	0.02	11	1440	<2	<5	<20	88	0.11	<10	242	<10	<1	73
3	A96 - 372	50	<0.2	3.63	45	60	<5	4.24	<1	30	26	99	7.77	<10	3.99	1306	7	0.02	12	1450	<2	<5	<20	77	0.14	<10	265	<10	<1	40
4	A96 - 373	45	<0.2	3.49	30	65	<5	4.10	<1	33	33	129	7.77	<10	3.99	1529	<1	0.01	12	1830	<2	<5	<20	73	0.14	<10	265	<10	1	55
5	A96 - 374	100	<0.2	3.45	85	50	<5	8.01	<1	36	21	167	8.57	<10	3.88	1838	12	0.01	12	1840	<2	<5	<20	107	0.08	<10	270	<10	<1	103
6	A96 - 375	70	<0.2	2.79	30	45	<5	5.20	<1	30	22	91	6.89	<10	2.91	1257	6	0.02	10	1530	<2	<5	<20	119	0.06	<10	236	<10	<1	56
7	A96 - 376	140	<0.2	2.99	<5	55	<5	4.78	<1	22	19	68	6.84	<10	2.86	1277	4	0.02	10	1340	<2	<5	<20	83	0.03	<10	228	<10	<1	53
8	A96 - 377	460	0.2	1.84	160	55	<5	3.67	<1	99	24	107	4.78	<10	1.46	876	2	0.02	3	1170	<2	<5	<20	55	0.02	<10	139	<10	<1	48
9	A96 - 378	600	0.4	2.16	225	80	<5	2.46	<1	178	18	148	5.10	<10	1.71	1001	3	0.02	<1	1470	<2	<5	<20	39	0.01	<10	97	<10	<1	58
10	A96 - 379	250	0.6	1.88	150	90	<5	0.79	<1	46	22	108	5.34	<10	1.24	609	8	0.03	3	1770	<2	<5	<20	15	<0.01	<10	58	<10	<1	57
11	A96 - 380	995	1.6	1.87	820	75	<5	3.75	<1	145	30	715	6.12	<10	1.24	981	17	0.02	6	1410	16	<5	<20	53	0.02	<10	59	<10	<1	78
12	A96 - 381	610	1.0	1.54	810	80	<5	1.65	<1	42	48	196	5.71	<10	0.92	669	6	0.01	4	1120	6	<5	<20	26	0.03	<10	47	<10	<1	52
13	A96 - 382	50	0.2	1.70	25	70	<5	2.16	<1	25	32	123	5.00	<10	1.10	780	11	0.03	5	1840	<2	<5	<20	34	0.03	<10	66	<10	<1	63
14	A96 - 383	20	1.0	2.41	35	125	<5	4.94	3	21	39	47	6.48	<10	1.11	2178	9	<0.01	7	1320	24	<5	<20	101	<0.01	<10	55	<10	<1	242
15	A96 - 384	15	4.6	3.65	160	65	90	5.83	1	25	48	167	>10	<10	1.76	3014	19	<0.01	12	830	52	<5	<20	122	0.01	<10	341	<10	<1	306
16	A96 - 385	25	2.8	3.13	125	75	<5	8.78	4	30	46	177	>10	<10	1.56	3921	21	<0.01	18	1500	40	<5	<20	136	0.01	<10	226	<10	<1	333
17	A96 - 386	45	2.0	1.72	35	70	<5	8.41	2	37	22	76	7.59	<10	0.82	2705	10	<0.01	13	1760	20	<5	<20	167	<0.01	<10	79	<10	<1	150
18	A96 - 387	>1000	5.2	3.64	1535	85	<5	2.02	<1	322	9	709	>10	<10	1.97	998	14	<0.01	10	1340	<2	<5	<20	29	0.05	<10	116	<10	<1	160
19	A96 - 388	230	<0.2	2.31	45	75	<5	2.39	<1	41	21	73	5.10	<10	1.64	671	<1	<0.01	5	1280	<2	<5	<20	36	0.09	<10	66	<10	1	57
20	A96 - 389	275	<0.2	1.59	80	60	<5	4.53	<1	31	41	129	4.37	<10	1.13	758	<1	0.02	8	1570	6	<5	<20	66	0.09	<10	117	<10	1	54

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
QC/DATA:																															
Resplit:																															
1	A96 - 370	>1000	<0.2	3.15	125	65	<5	3.65	<1	66	36	296	8.63	<10	2.73	1049	12	0.02	14	1350	<2	<5	<20	43	0.07	<10	237	<10	<1	62	
Repeat:																															
1	A96 - 370	>1000	<0.2	3.40	170	70	<5	3.65	<1	67	38	322	8.52	<10	2.95	1047	10	0.02	15	1410	<2	<5	<20	50	0.08	<10	248	<10	<1	64	
10	A96 - 379	260	0.6	1.78	150	90	<5	0.77	<1	45	21	98	5.22	<10	1.16	594	8	0.02	4	1730	4	<5	<20	14	<0.01	<10	56	<10	<1	58	
19	A96 - 388	205																													
Standard:																															
GEO'96																															
		150	1.2	1.79	65	145	<5	2.07	<1	21	72	71	4.08	<10	0.95	778	<1	0.02	24	750	18	<5	<20	54	0.14	<10	86	<10	4	69	

dt/5286
XLS/96Teuton


ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5290

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700

Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received:30

Sample Type:ROCK

PROJECT #:NOT GIVEN

SHIPMENT #:NOT GIVEN

P.O.#: NOT GIVEN

Samples submitted by:NOT GIVEN

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	A96 - 341	5	1.4	0.18	65	35	<5	>10	9	9	40	12	1.59	<10	0.08	3077	3	<0.01	10	240	14	<5	<20	218	0.01	<10	8	<10	5	812
2	A96 - 342	5	0.4	2.42	10	190	<5	>10	<1	14	57	68	8.98	<10	0.62	2518	9	<0.01	12	<10	<2	<5	<20	107	0.02	<10	121	<10	<1	163
3	A96 - 343	5	<0.2	1.31	<5	680	<5	1.38	1	10	32	19	4.67	<10	0.67	534	2	0.02	13	1370	2	<5	<20	80	0.04	<10	41	<10	5	84
4	A96 - 344	5	1.0	0.53	25	305	<5	>10	21	11	35	27	1.96	<10	0.37	3933	2	<0.01	10	500	60	10	<20	212	0.07	<10	40	<10	4	118
5	A96 - 345	5	<0.2	0.06	<5	1615	<5	0.52	<1	<1	371	5	1.35	<10	0.01	208	2	<0.01	7	<10	4	<5	<20	30	<0.01	<10	31	<10	<1	11
6	A96 - 346	5	1.0	0.08	15	30	<5	>10	12	<1	5	1	0.64	<10	0.18	4546	1	<0.01	<1	290	16	10	<20	1801	0.01	<10	5	<10	<1	589
7	A96 - 347	10	1.2	0.18	<5	10	<5	>10	2	<1	4	1	1.00	<10	0.23	6665	1	<0.01	<1	170	<2	15	<20	1515	0.02	<10	8	<10	<1	112
8	A96 - 348	180	1.6	0.13	20	535	<5	>10	5	<1	<1	4	1.11	<10	0.17	6103	3	<0.01	3	50	<2	20	<20	1051	0.01	<10	8	<10	<1	226
9	A96 - 349	580	11.0	1.14	1965	150	30	0.28	<1	29	<1	73	>10	<10	<0.01	643	54	<0.01	7	<10	1832	<5	<20	11	<0.01	<10	224	<10	<1	7216
10	A96 - 350	5	<0.2	1.17	15	210	15	2.39	1	18	26	4	5.66	<10	0.47	732	<1	0.01	5	360	28	<5	<20	87	0.35	<10	47	<10	17	112
11	A96 - 351	5	<0.2	1.28	<5	230	5	2.04	2	12	28	21	6.41	20	0.33	421	6	<0.01	3	1170	28	<5	<20	203	0.03	<10	46	<10	8	107
12	A96 - 352	5	0.4	1.99	<5	120	<5	6.25	2	14	36	4	4.73	<10	1.03	2106	6	<0.01	4	1470	<2	<5	<20	107	<0.01	<10	32	<10	<1	92
13	A96 - 353	60	1.6	2.04	20	80	10	4.41	2	16	33	10	4.81	<10	1.11	1722	5	<0.01	6	1510	6	<5	<20	117	<0.01	<10	40	<10	<1	101
14	A96 - 354	5	3.4	2.98	115	195	<5	2.35	2	31	44	221	9.08	<10	1.84	3881	12	<0.01	19	1810	32	<5	<20	38	0.01	<10	84	<10	<1	238
15	A96 - 355	10	2.4	3.16	25	85	<5	4.75	2	32	47	145	8.95	<10	1.94	1706	10	<0.01	15	1720	6	<5	<20	61	<0.01	<10	80	<10	<1	229
16	A96 - 356	140	3.0	2.81	60	85	<5	2.78	2	39	24	95	>10	<10	1.56	1455	19	<0.01	14	1730	30	<5	<20	36	<0.01	<10	74	<10	<1	285
17	A96 - 357	5	3.2	3.61	40	105	<5	3.37	11	35	34	125	9.56	<10	2.46	1868	13	<0.01	12	1830	290	<5	<20	43	<0.01	<10	100	<10	<1	812
18	A96 - 358	30	1.0	2.73	25	180	<5	3.86	3	21	26	17	5.93	<10	1.54	1525	8	<0.01	10	1580	34	<5	<20	55	<0.01	<10	70	<10	<1	365
19	A96 - 359	10	0.8	3.34	<5	360	<5	2.87	7	26	26	19	7.18	<10	1.89	1599	6	<0.01	15	1790	34	<5	<20	36	<0.01	<10	93	<10	<1	459
20	A96 - 360	5	3.2	2.48	115	60	<5	7.55	<1	26	27	83	8.16	<10	1.64	2047	12	<0.01	11	1450	20	<5	<20	101	<0.01	<10	60	<10	<1	186
21	A96 - 361	45	3.6	2.22	45	55	<5	7.09	2	28	32	88	8.17	<10	1.49	2047	14	<0.01	14	1450	76	<5	<20	99	<0.01	<10	54	<10	<1	279
22	A96 - 362	300	11.2	2.39	120	75	<5	1.86	1	34	33	191	9.59	<10	1.45	863	12	<0.01	16	1500	1308	<5	<20	33	<0.01	<10	64	<10	<1	307
23	A96 - 363	30	4.2	2.97	70	85	<5	0.96	1	40	27	103	>10	<10	1.70	916	14	<0.01	16	2060	116	<5	<20	11	<0.01	<10	93	<10	<1	404
24	A96 - 364	95	4.8	2.84	230	65	<5	0.66	<1	36	21	87	9.66	<10	1.58	856	15	<0.01	15	1750	158	<5	<20	11	<0.01	<10	75	<10	<1	373
25	A96 - 365	20	1.4	2.11	20	80	<5	1.25	3	19	21	20	5.81	<10	1.13	708	7	<0.01	12	1670	42	<5	<20	22	<0.01	<10	47	<10	<1	322

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	A96 - 366	50	3.4	3.21	80	90	<5	1.20	1	45	17	377	9.18	<10	1.84	917	12	<0.01	11	1510	24	<5	<20	21	<0.01	<10	78	<10	<1	220
27	A96 - 367	10	2.4	3.18	110	130	<5	0.48	<1	26	26	200	7.89	<10	1.98	1185	9	<0.01	11	1620	28	<5	<20	10	<0.01	<10	93	<10	<1	231
28	A96 - 368	30	1.2	2.53	105	95	<5	5.30	9	19	28	18	6.99	<10	1.37	1801	6	<0.01	5	1320	30	<5	<20	62	<0.01	<10	49	<10	<1	245
29	A96 - 369	5	0.6	3.61	15	265	<5	4.44	1	26	12	98	7.72	<10	2.42	1762	6	<0.01	7	1440	<2	<5	<20	65	<0.01	<10	85	<10	<1	215
30	A96 - 390	830	6.0	1.76	<5	95	<5	0.16	3	31	68	1343	>10	<10	1.12	720	26	<0.01	27	90	2	<5	<20	5	0.11	<10	146	<10	<1	77

QC/DATA:**Resplit:**

12	A96 - 352	5	0.4	2.02	<5	115	5	5.99	2	14	35	10	4.50	<10	1.04	2000	3	<0.01	3	1410	<2	<5	<20	110	<0.01	<10	31	<10	<1	87
----	-----------	---	-----	------	----	-----	---	------	---	----	----	----	------	-----	------	------	---	-------	---	------	----	----	-----	-----	-------	-----	----	-----	----	----


Repeat:

1	A96 - 341	5	1.6	0.18	75	45	<5	>10	12	12	51	13	1.65	<10	0.08	3194	4	<0.01	12	260	24	<5	<20	221	0.01	<10	10	<10	7	809
10	A96 - 350	5	<0.2	1.19	5	205	5	2.11	<1	17	24	4	5.36	<10	0.49	681	<1	0.01	3	310	24	<5	<20	91	0.36	<10	46	<10	16	105
19	A96 - 359	15	0.8	3.30	<5	330	10	2.79	7	27	26	20	7.00	<10	1.88	1557	6	<0.01	15	1810	38	<5	<20	35	<0.01	<10	90	<10	<1	441

Standard:

GEO'96		140	1.4	1.98	60	160	<5	2.04	1	22	75	81	4.14	<10	1.13	728	4	0.02	24	780	18	5	<20	60	0.14	<10	87	<10	4	76
--------	--	-----	-----	------	----	-----	----	------	---	----	----	----	------	-----	------	-----	---	------	----	-----	----	---	-----	----	------	-----	----	-----	---	----

dl/5290
XLS/96Teuton


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5312

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

27-Sep-96

ATTENTION: DINO CREMONESE


No. of samples received: 19
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: NOT GIVEN
P.O. #: NOT GIVEN
Samples submitted by: ALEX WALIS

ET #.	Tag #	Au (g/t)	Au (oz/t)	Co (%)
1	ERK-96- 240	1.15	0.034	0.088
12	ERK-96- 251	13.92	0.406	-
13	ERK-96- 252	2.93	0.085	0.050
17	A-96- 394	5.56	0.162	-
18	A-96- 395	8.46	0.247	-

QC/DATA:

Standard:

Su1a - - 0.041


ECC-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/96Teuton#8
Fax @: 604-636-2839/D.Cremonese

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5312

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 19
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: NOT GIVEN
P.O.#: NOT GIVEN
Samples submitted by: ALEX WALIS

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	ERK-96- 240	>1000	1.0	4.12	6385	60	<5	5.75	<1	670	36	255	>10	<10	3.85	1424	17	<0.01	14	1640	50	<5	<20	109	0.02	<10	245	<10	<1	48
2	ERK-96- 241	90	0.4	3.79	245	55	<5	4.74	<1	41	13	198	9.15	<10	3.30	1186	8	0.01	8	1850	18	<5	<20	98	0.01	<10	235	<10	<1	43
3	ERK-96- 242	10	<0.2	4.06	35	65	5	4.24	<1	22	5	96	8.47	<10	3.62	1167	6	0.01	7	1980	10	<5	<20	84	0.02	<10	239	<10	<1	42
4	ERK-96- 243	690	0.4	3.77	1125	50	<5	4.08	<1	115	5	233	8.98	<10	3.39	1060	7	0.01	6	1960	26	<5	<20	145	0.02	<10	229	<10	<1	43
5	ERK-96- 244	350	0.2	4.29	265	60	<5	4.08	<1	43	20	161	9.59	<10	3.96	1239	7	0.02	8	1960	20	<5	<20	97	0.02	<10	251	<10	<1	52
6	ERK-96- 245	435	0.4	3.43	50	60	<5	8.77	2	24	27	174	7.76	<10	3.15	2085	17	0.02	7	1550	20	<5	<20	168	0.02	<10	221	<10	9	42
7	ERK-96- 246	10	<0.2	4.41	25	75	<5	6.00	<1	28	27	90	7.95	<10	4.31	1443	5	<0.01	13	1780	18	<5	<20	146	0.01	<10	181	<10	<1	76
8	ERK-96- 247	770	1.6	3.75	1980	55	<5	5.37	3	142	9	349	9.76	<10	3.27	1535	8	0.01	9	1610	72	<5	<20	126	0.02	<10	200	<10	<1	454
9	ERK-96- 248	95	0.2	3.70	90	45	<5	9.03	2	22	3	109	8.34	<10	3.15	2094	7	0.01	4	1650	14	<5	<20	175	0.02	<10	211	<10	5	46
10	ERK-96- 249	25	0.6	3.65	15	50	<5	8.93	7	24	6	183	8.37	<10	3.19	2224	8	0.01	5	1620	24	<5	<20	154	0.02	<10	201	<10	7	50
11	ERK-96- 250	25	<0.2	1.94	35	80	<5	5.48	<1	9	37	56	4.33	<10	1.36	931	4	0.02	8	1710	16	<5	<20	211	<0.01	<10	86	<10	<1	42
12	ERK-96- 251	>1000	5.4	3.01	3250	50	<5	6.43	<1	123	25	557	>10	<10	2.20	1111	59	<0.01	13	1130	40	<5	<20	154	<0.01	<10	131	<10	<1	78
13	ERK-96- 252	>1000	0.8	2.21	5265	50	<5	5.25	<1	464	35	224	6.97	<10	1.76	943	15	<0.01	12	1690	20	<5	<20	146	<0.01	<10	87	<10	<1	57
14	A-96- 391	5	<0.2	4.86	20	90	<5	6.28	<1	33	43	85	8.21	<10	5.40	1529	4	<0.01	16	1620	16	<5	<20	166	0.02	<10	262	<10	<1	88
15	A-96- 392	5	<0.2	5.61	5	140	5	5.71	<1	33	42	95	9.76	<10	5.95	1570	5	<0.01	16	1660	18	<5	<20	133	0.02	<10	260	<10	<1	133
16	A-96- 393	10	<0.2	4.90	15	140	<5	6.19	<1	37	45	90	8.38	<10	5.12	1578	5	<0.01	16	1630	14	<5	<20	143	0.02	<10	219	<10	<1	92
17	A-96- 394	>1000	1.4	2.63	540	185	<5	1.78	<1	130	27	139	6.60	<10	1.80	1162	6	<0.01	10	1840	22	<5	<20	40	0.01	<10	98	<10	<1	81
18	A-96- 395	>1000	1.8	2.89	360	80	<5	4.90	<1	110	24	224	7.96	<10	1.52	996	7	<0.01	5	1170	22	<5	<20	99	0.01	<10	93	<10	<1	74
19	A-96- 396	35	0.4	1.72	65	65	<5	4.28	<1	21	27	80	4.42	<10	1.03	858	3	0.02	4	1120	16	<5	<20	83	0.04	<10	55	<10	1	39

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
-------	-------	---------	----	------	----	----	----	------	----	----	----	----	------	----	------	----	----	------	----	---	----	----	----	----	------	---	---	---	---	----

QC/DATA:


Repeat:

1	ERK-96- 240	>1000	1.0	4.20	6600	60	<5	5.92	<1	679	37	256	>10	<10	3.89	1460	18	<0.01	14	1700	58	<5	<20	109	0.02	<10	249	<10	<1	48
10	ERK-96- 249	35	0.4	3.66	20	50	<5	8.93	7	24	6	183	8.39	<10	3.17	2226	8	0.01	5	1650	24	<5	<20	155	0.02	<10	201	<10	8	51
19	A-96- 396	30	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

Standard:

GEO'96		150	1.2	2.06	50	165	<5	1.97	<1	21	71	80	4.12	<10	1.08	720	<1	0.02	25	730	26	<5	<20	65	0.14	<10	90	<10	4	69
--------	--	-----	-----	------	----	-----	----	------	----	----	----	----	------	-----	------	-----	----	------	----	-----	----	----	-----	----	------	-----	----	-----	---	----

d//5312
XLS/96Teuton


 ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5291

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2


17-Sep-96

ATTENTION: DINO CREMONESE

No. of samples received: 9
Sample Type: Rock
PROJECT #: Clone
SHIPMENT #: S96-51
P.O.#: None Given
Samples submitted by: David Hick

ET #.	Tag #	Au (g/t)	Au (oz/t)
5	D96-379	5.97	0.174
6	D96-380	1.41	0.041

XLS/96Teuton#7


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5291

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 9

Sample Type: Rock

PROJECT #: Clone

SHIPMENT #: S96-51

P.O.#: None Given

Samples submitted by: David Hick

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	D96-375	530	2.2	2.48	590	100	<5	2.60	<1	33	52	296	>10	<10	1.28	1772	27	<0.01	39	1610	30	<5	<20	34	0.01	<10	93	<10	<1	64
2	D96-376	215	1.2	3.22	105	125	<5	3.58	<1	19	63	151	8.55	<10	1.98	1330	7	<0.01	20	2200	28	<5	<20	57	0.01	<10	108	<10	<1	48
3	D96-377	5	0.4	2.46	<5	100	<5	6.40	<1	17	63	55	5.82	<10	1.25	1285	5	<0.01	5	1510	16	<5	<20	138	<0.01	<10	73	<10	2	31
4	D96-378	5	<0.2	2.46	10	155	<5	3.34	<1	16	71	61	6.10	<10	1.28	1132	5	0.01	6	1710	18	<5	<20	62	<0.01	<10	78	<10	1	34
5	D96-379	>1000	4.0	1.48	9505	80	<5	1.61	<1	43	65	1051	>10	<10	0.54	526	16	<0.01	20	1390	14	<5	<20	25	<0.01	10	37	<10	<1	24
6	D96-380	>1000	1.2	1.48	3575	40	<5	3.75	<1	22	35	185	7.71	<10	0.80	822	7	<0.01	13	1790	12	<5	<20	52	<0.01	<10	38	<10	<1	21
7	D96-381	750	0.6	2.35	445	60	5	5.23	<1	25	94	84	8.78	<10	1.56	1136	7	<0.01	25	1770	28	<5	<20	72	0.01	<10	85	<10	<1	33
8	D96-382	695	0.8	1.83	400	50	<5	5.81	<1	21	59	95	6.86	<10	1.05	1121	8	<0.01	21	1790	22	<5	<20	68	<0.01	<10	59	<10	<1	46
9	D96-383	245	1.0	3.00	510	80	<5	4.50	<1	38	84	129	9.16	<10	1.93	1358	9	<0.01	25	1890	32	<5	<20	53	0.01	<10	93	<10	<1	49

QC/DATA:**Resplit:**


R/S 1	D96-375	535	2.2	2.36	605	90	<5	2.42	<1	32	46	268	>10	<10	1.10	1619	20	<0.01	35	1560	36	<5	<20	29	0.01	<10	81	<10	<1	66
-------	---------	-----	-----	------	-----	----	----	------	----	----	----	-----	-----	-----	------	------	----	-------	----	------	----	----	-----	----	------	-----	----	-----	----	----

Repeat:

1	D96-375	520	2.0	2.26	545	85	<5	2.54	<1	30	47	280	>10	<10	1.11	1720	20	<0.01	32	1550	36	<5	<20	31	0.01	<10	80	<10	<1	61
---	---------	-----	-----	------	-----	----	----	------	----	----	----	-----	-----	-----	------	------	----	-------	----	------	----	----	-----	----	------	-----	----	-----	----	----

Standard:

GEO'96		150	1.4	1.75	65	160	<5	1.86	<1	20	66	80	4.06	<10	0.82	728	2	0.01	24	710	20	10	<20	60	0.10	<10	75	<10	5	70
--------	--	-----	-----	------	----	-----	----	------	----	----	----	----	------	-----	------	-----	---	------	----	-----	----	----	-----	----	------	-----	----	-----	---	----


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

24-Sep-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5313

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 45
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: NONE GIVEN
P.O. #: NONE GIVEN
Samples submitted by: ALEX WALUS


Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	A96-397	140	<0.2	4.08	50	75	<5	6.29	<1	33	28	99	8.13	<10	3.61	1529	5	<0.01	10	1900	16	<5	<20	160	0.02	<10	144	<10	<1	84
2	A96-398	180	0.4	4.53	300	65	<5	5.49	3	51	34	101	9.40	<10	4.62	1715	6	<0.01	9	2000	186	<5	<20	160	0.03	<10	287	<10	<1	319
3	A96-399	40	<0.2	4.25	30	50	<5	5.09	<1	34	39	168	8.96	<10	4.55	1563	6	0.01	12	1870	22	<5	<20	146	0.02	<10	270	<10	<1	72
4	A96-400	325	0.2	2.22	2170	45	<5	5.59	<1	32	31	178	6.13	<10	2.17	1137	6	0.02	5	1070	16	<5	<20	154	0.01	<10	113	<10	<1	43
5	A96-584	80	<0.2	4.14	960	70	<5	3.87	<1	41	17	123	8.73	<10	4.12	1692	7	0.01	11	2100	24	<5	<20	93	0.02	<10	224	<10	<1	88
6	A96-585	15	<0.2	4.35	45	50	<5	4.34	<1	30	9	134	8.64	<10	4.42	1450	5	0.01	8	1990	20	<5	<20	106	0.02	<10	246	<10	<1	81
7	A96-586	65	<0.2	4.45	25	65	5	3.70	<1	34	12	109	8.78	<10	4.51	1381	6	0.02	10	2120	24	<5	<20	96	0.02	<10	246	<10	<1	79
8	A96-587	150	<0.2	3.77	145	60	<5	4.40	<1	34	5	163	8.08	<10	3.41	1135	6	0.01	8	2100	20	<5	<20	127	0.02	<10	178	<10	<1	58
9	A96-588	535	<0.2	3.77	160	55	<5	5.94	<1	25	18	116	7.99	<10	3.30	1258	11	0.01	6	1840	16	<5	<20	145	0.01	<10	172	<10	<1	45
10	A96-589	55	0.2	3.49	45	55	<5	7.58	<1	24	20	161	7.94	<10	3.07	1480	6	0.01	10	1800	18	<5	<20	163	0.01	<10	170	<10	<1	41
11	A96-601	20	<0.2	5.01	15	55	<5	4.48	<1	35	25	117	>10	<10	5.16	1698	6	0.01	12	1940	26	<5	<20	137	0.03	<10	290	<10	<1	92
12	A96-602	235	0.4	4.57	140	50	<5	5.04	5	32	40	169	9.92	<10	4.44	1585	7	0.01	13	1960	188	<5	<20	152	0.02	<10	282	<10	<1	406
13	A96-603	50	<0.2	4.48	55	65	<5	5.64	1	32	32	140	9.76	<10	3.88	1559	10	<0.01	15	1820	70	<5	<20	192	0.02	<10	228	<10	<1	111
14	A96-604	330	0.6	4.17	1370	60	<5	7.02	<1	109	24	258	>10	<10	3.37	1450	9	<0.01	13	1480	30	<5	<20	181	0.02	<10	184	<10	<1	75
15	A96-605	35	<0.2	3.69	60	75	<5	7.53	<1	29	41	132	7.45	<10	3.22	1674	5	<0.01	14	1820	16	<5	<20	180	0.02	<10	165	<10	<1	85
16	A96-606	255	<0.2	4.32	1445	80	<5	5.19	<1	163	18	96	9.51	<10	3.64	1419	6	0.01	11	2010	26	<5	<20	116	0.02	<10	181	<10	<1	100
17	A96-607	70	0.4	3.38	55	55	<5	7.70	<1	45	32	231	9.18	<10	2.61	1638	7	0.01	17	1940	26	<5	<20	171	0.01	<10	155	<10	<1	66
18	A96-608	85	0.4	3.15	105	40	<5	>10	<1	37	18	216	8.75	<10	2.38	1950	8	<0.01	12	1590	22	<5	<20	205	<0.01	<10	110	<10	<1	59
19	A96-609	40	0.6	3.02	25	35	<5	9.93	<1	30	19	185	7.76	<10	2.06	1768	7	<0.01	12	1750	20	<5	<20	200	0.01	<10	92	<10	<1	58
20	A96-610	65	0.4	2.24	855	40	<5	>10	<1	33	12	194	6.65	<10	1.69	2718	8	<0.01	12	1310	20	<5	<20	284	<0.01	<10	77	<10	<1	62
21	A96-611	20	<0.2	4.19	20	120	10	7.59	<1	26	23	97	8.93	<10	3.06	1619	6	<0.01	13	1790	22	<5	<20	152	0.01	<10	140	<10	<1	109
22	A96-612	55	<0.2	4.06	60	90	<5	8.59	<1	27	23	80	8.91	<10	2.92	1755	6	<0.01	11	1770	24	<5	<20	170	0.01	<10	140	<10	<1	115
23	A96-613	265	0.2	4.11	20	85	10	>10	1	18	26	43	9.54	<10	2.77	2243	7	<0.01	11	1440	28	<5	<20	348	0.01	<10	148	<10	<1	129
24	A96-614	260	0.4	3.05	30	110	5	>10	3	25	32	77	7.15	<10	1.77	2314	7	<0.01	13	1550	26	<5	<20	210	<0.01	<10	98	<10	<1	156
25	A96-615	45	0.2	3.74	25	105	10	>10	1	25	29	51	8.08	<10	2.50	2487	6	<0.01	13	1400	26	<5	<20	292	<0.01	<10	122	<10	<1	120

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sh	Sn	Sr	Ti %	U	V	W	Y	Zn
26	A96-616	215	10.8	2.12	3930	45	<5	3.69	<1	38	24	54	5.37	<10	1.35	1536	8	<0.01	5	1120	340	<5	<20	62	<0.01	<10	51	<10	<1	663
27	A96-617	20	2.6	1.96	70	80	<5	2.58	15	19	27	59	4.97	<10	1.25	1476	8	<0.01	4	1130	138	<5	<20	33	<0.01	<10	51	<10	<1	653
28	A96-618	10	0.4	2.17	25	50	5	4.78	<1	14	16	23	5.57	<10	1.50	1243	6	<0.01	3	980	26	<5	<20	78	<0.01	<10	54	<10	<1	174
29	A96-619	45	0.6	2.45	45	30	5	4.50	1	21	22	65	7.05	<10	1.67	1245	6	<0.01	5	1170	34	<5	<20	74	<0.01	<10	67	<10	<1	167
30	A96-620	310	1.2	2.01	280	40	<5	4.83	2	35	18	175	9.05	<10	1.34	1350	12	<0.01	4	810	62	<5	<20	82	<0.01	<10	46	<10	<1	197
31	A96-621	155	2.8	1.91	595	40	<5	5.57	<1	20	20	72	5.67	<10	1.29	1396	6	<0.01	3	930	124	<5	<20	85	<0.01	<10	43	<10	<1	136
32	A96-622	5	0.8	2.11	60	40	<5	6.19	1	16	15	33	5.38	<10	1.44	1610	6	<0.01	2	1020	42	<5	<20	93	<0.01	<10	47	<10	<1	168
33	A96-623	5	1.8	2.04	130	50	<5	5.69	4	17	22	47	5.45	<10	1.15	1813	6	<0.01	3	1160	80	<5	<20	81	<0.01	<10	47	<10	<1	279
34	A96-624	55	4.4	2.03	250	50	<5	7.48	19	16	24	76	6.09	<10	1.02	4067	7	<0.01	4	890	470	<5	<20	110	<0.01	<10	51	<10	<1	1273
35	A96-625	15	1.8	2.11	190	95	<5	4.00	4	17	14	81	5.55	<10	0.80	2353	5	<0.01	5	1310	94	<5	<20	60	<0.01	<10	43	<10	<1	322
36	A96-626	15	1.0	2.31	495	55	5	5.10	2	17	23	52	6.24	<10	1.15	2451	5	<0.01	6	1160	66	<5	<20	80	<0.01	<10	61	<10	<1	230
37	A96-627	5	0.6	2.26	85	45	<5	5.04	<1	19	28	65	5.53	<10	1.60	1649	7	<0.01	4	1340	42	<5	<20	81	<0.01	<10	65	<10	<1	78
38	A96-628	40	1.0	2.68	25	55	<5	6.23	2	33	59	106	7.62	<10	2.23	1764	8	<0.01	15	1340	60	<5	<20	96	<0.01	<10	101	<10	<1	85
39	A96-629	10	1.4	2.62	50	70	<5	4.10	2	23	22	86	7.07	<10	0.94	2405	8	<0.01	11	1870	78	<5	20	60	<0.01	<10	66	<10	<1	174
40	A96-630	10	1.6	2.37	40	75	<5	1.64	3	25	21	107	6.37	<10	0.75	1311	9	<0.01	14	2340	86	<5	<20	22	<0.01	<10	55	<10	<1	205
41	A96-631	5	1.8	2.53	180	60	<5	3.30	7	25	17	75	6.96	<10	0.89	1869	7	<0.01	8	1640	152	<5	20	44	<0.01	<10	66	<10	<1	456
42	A96-632	5	1.4	2.35	40	80	<5	5.99	5	20	23	61	5.72	<10	0.98	2431	7	<0.01	6	1300	76	<5	<20	84	<0.01	<10	41	<10	<1	275
43	A96-633	10	0.8	2.57	60	35	<5	5.40	<1	15	13	41	5.45	<10	1.92	1305	5	<0.01	4	1310	46	<5	<20	109	<0.01	<10	62	<10	<1	94
44	A96-634	5	0.2	2.90	60	45	10	6.06	1	24	32	69	8.11	<10	2.06	1323	7	<0.01	7	1450	40	<5	<20	104	<0.01	<10	98	<10	<1	113
45	A96-635	100	1.2	1.95	420	40	<5	1.00	9	26	48	126	>10	<10	1.23	629	14	<0.01	7	1170	82	<5	40	19	<0.01	<10	77	<10	<1	190

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
QC/DATA:																															
<i>Resplit:</i>																															
1	A96-397	135	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
36	A96-626	10	1.0	2.39	415	50	5	5.12	4	18	22	54	6.75	<10	1.19	2411	6	<0.01	6	1230	76	<5	<20	81	<0.01	<10	63	<10	<1	239	
<i>Repeat:</i>																															
1	A96-397	155	<0.2	3.94	50	70	<5	6.14	<1	32	27	94	7.91	<10	3.47	1484	6	<0.01	9	1870	20	<5	<20	152	0.02	<10	137	<10	<1	84	
10	A96-589	50	<0.2	3.47	50	50	<5	7.65	<1	24	21	160	8.06	<10	3.06	1494	7	0.01	11	1850	18	<5	<20	161	0.01	<10	170	<10	<1	43	
16	A96-606	250	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
19	A96-609	-	0.4	2.89	35	30	<5	9.72	<1	30	18	175	7.62	<10	1.97	1731	7	<0.01	12	1760	26	<5	<20	192	<0.01	<10	88	<10	<1	62	
25	A96-615	65	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
34	A96-624	60	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
36	A96-626	-	1.0	2.40	495	50	5	5.24	2	17	23	52	6.41	<10	1.18	2483	6	<0.01	6	1200	66	<5	<20	82	<0.01	<10	63	<10	<1	235	
<i>Standard:</i>																															
GEO'96		145	1.2	1.94	60	155	<5	2.02	<1	21	63	71	4.08	<10	1.04	740	<1	0.02	23	740	24	<5	<20	61	0.12	<10	82	<10	2	78	
GEO'9		150	1.2	1.89	95	140	<5	2.05	<1	20	65	70	4.70	<10	0.97	713	<1	0.02	24	740	24	<5	<20	59	0.13	<10	81	<10	2	76	

df/5312
XLS/96Teuton


 ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.
 B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5300

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

18-Sep-96

ATTENTION: DINO CREMONESE

No. of samples received: 31

Sample Type: Rock

PROJECT #: Clone

SHIPMENT #: S96-52

P.O.#: None Given

Samples submitted by: David Hick

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	As (%)	Cu (%)
8	D96-391	1.41	0.041	-	-	-	-
11	D96-394	1.23	0.036	-	-	-	-
18	D96-401	5.94	0.173	55.0	1.60	-	2.33
19	D96-402	15.11	0.441	113.0	3.30	-	2.89
20	D96-403	2.91	0.085	466.0	13.59	-	14.40
21	D96-404	1.36	0.040	174.2	5.08	-	6.90
24	D96-407	4.82	0.141	-	-	-	-
25	D96-408	5.27	0.154	-	-	2.50	-
26	D96-409	5.62	0.164	-	-	-	-
28	D96-411	3.04	0.089	-	-	-	-
29	D96-412	2.07	0.060	-	-	-	-

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

XLS/96Teuton#8

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5300

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 31
Sample Type: Rock...
PROJECT #: Clone
SHIPMENT #: S96-52
P.O.#: None Given
Samples submitted by: David Hick

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	D96-384	550	0.6	1.11	415	40	10	0.50	<1	50	93	47	>10	<10	0.58	372	13	<0.01	41	1000	28	<5	<20	8	<0.01	<10	30	<10	<1	16
2	D96-385	115	<0.2	1.38	125	70	<5	2.49	<1	21	98	17	4.59	<10	0.85	707	6	<0.01	21	1210	22	<5	<20	55	<0.01	<10	39	<10	<1	16
3	D96-386	465	0.6	1.75	285	90	<5	2.36	<1	28	99	165	>10	<10	1.10	919	11	<0.01	31	940	30	<5	<20	40	<0.01	<10	51	<10	<1	27
4	D96-387	10	<0.2	1.52	20	115	<5	5.33	<1	10	62	16	3.42	<10	0.86	1190	4	<0.01	12	1250	18	<5	<20	85	<0.01	<10	38	<10	1	25
5	D96-388	5	<0.2	1.62	15	170	<5	3.85	<1	7	62	34	3.85	<10	0.64	1284	2	<0.01	7	1350	18	<5	<20	66	<0.01	<10	34	<10	<1	22
6	D96-389	90	<0.2	1.12	55	55	10	1.51	<1	16	64	9	3.67	<10	0.54	593	6	<0.01	9	1210	18	<5	<20	32	<0.01	<10	25	<10	<1	15
7	D96-390	830	0.8	0.57	680	45	15	0.83	<1	24	147	29	>10	<10	0.19	306	23	<0.01	12	570	24	<5	<20	10	<0.01	<10	14	<10	<1	34
8	D96-391	>1000	3.0	0.70	385	40	<5	1.25	<1	22	101	441	>10	<10	0.33	421	21	<0.01	14	590	28	<5	<20	20	<0.01	<10	18	<10	<1	16
9	D96-392	260	<0.2	1.02	50	75	<5	2.25	<1	9	130	24	3.43	<10	0.52	753	4	<0.01	8	830	24	<5	<20	85	<0.01	<10	26	<10	<1	15
10	D96-393	90	<0.2	1.84	40	115	<5	3.26	<1	15	75	44	4.62	<10	1.00	984	9	<0.01	13	1380	32	<5	<20	56	<0.01	<10	55	<10	<1	44
11	D96-394	>1000	0.8	1.12	865	75	<5	2.57	<1	14	117	86	4.31	<10	0.58	679	17	<0.01	8	870	28	<5	<20	52	<0.01	<10	26	<10	<1	27
12	D96-395	580	0.4	0.56	305	35	<5	1.89	<1	16	43	241	8.57	<10	0.23	332	10	<0.01	11	1160	10	<5	<20	29	<0.01	<10	16	<10	<1	11
13	D96-396	120	<0.2	1.76	110	50	<5	2.59	<1	16	86	144	5.41	<10	1.12	698	4	<0.01	15	1270	30	<5	<20	42	<0.01	<10	62	<10	<1	26
14	D96-397	10	<0.2	2.12	70	65	<5	6.44	<1	20	90	98	4.86	<10	1.56	989	4	<0.01	31	1430	40	<5	<20	101	<0.01	<10	92	<10	<1	46
15	D96-398	300	3.0	2.23	<5	50	<5	0.28	<1	145	50	2159	>10	<10	1.54	572	41	<0.01	76	1050	40	<5	<20	9	0.07	<10	70	<10	<1	55
16	D96-399	455	4.6	2.02	10	50	<5	0.11	<1	166	61	4275	>10	<10	1.10	369	71	<0.01	70	740	36	<5	<20	8	0.06	<10	105	<10	<1	54
17	D96-400	555	5.4	2.08	15	50	<5	0.19	<1	71	79	2804	>10	<10	1.46	467	67	<0.01	31	850	44	<5	<20	13	0.10	<10	127	<10	<1	85
18	D96-401	>1000	>30	1.71	<5	45	<5	1.13	1	50	67	>10000	>10	<10	1.06	525	8665	<0.01	80	4570	34	<5	<20	15	0.08	<10	348	<10	<1	89
19	D96-402	>1000	>30	2.47	135	50	<5	0.47	<1	71	73	>10000	>10	<10	1.69	754	97	<0.01	25	3260	28	<5	<20	9	0.11	<10	249	<10	<1	79
20	D96-403	>1000	>30	0.82	250	70	<5	0.32	15	107	53	>10000	>10	<10	0.32	199	184	<0.01	51	>10000	306	<5	<20	6	<0.01	<10	68	<10	<1	689
21	D96-404	>1000	>30	2.56	95	50	<5	0.46	19	67	73	>10000	>10	<10	2.17	775	42	<0.01	43	>10000	20	<5	<20	8	<0.01	<10	205	<10	<1	718
22	D96-405	605	3.4	1.16	70	50	<5	0.08	<1	93	66	1283	>10	<10	0.38	143	29	<0.01	28	510	20	<5	<20	5	0.05	10	52	<10	<1	20
23	D96-406	155	0.6	1.58	525	45	<5	6.95	<1	29	103	208	6.83	<10	0.94	1729	8	<0.01	33	1440	34	<5	<20	92	<0.01	<10	63	<10	<1	48
24	D96-407	>1000	2.4	1.08	5715	55	<5	7.69	<1	20	82	390	5.82	<10	0.60	1689	5	<0.01	17	930	50	<5	<20	116	<0.01	<10	35	<10	<1	176
25	D96-408	>1000	8.6	1.12	>10000	40	<5	3.69	<1	31	59	1414	9.88	<10	0.62	1290	11	<0.01	20	1170	44	<5	<20	43	<0.01	<10	36	<10	<1	133

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	D96-409	>1000	3.8	0.55	4215	35	<5	1.99	<1	21	102	902	>10	<10	0.25	549	11	<0.01	19	790	10	<5	<20	30	<0.01	<10	18	<10	<1	16
27	D96-410	300	1.0	1.58	1345	45	<5	5.32	<1	17	93	578	4.68	<10	1.13	1197	4	<0.01	19	1620	28	<5	<20	61	<0.01	<10	65	<10	1	28
28	D96-411	>1000	2.6	1.27	3860	35	<5	6.90	<1	24	69	692	4.71	<10	0.93	1264	5	<0.01	22	1460	34	<5	<20	83	<0.01	<10	50	<10	<1	395
29	D96-412	>1000	0.6	2.03	1180	45	<5	6.77	<1	22	102	338	5.26	<10	1.46	1411	5	<0.01	27	1630	34	5	<20	75	0.01	<10	95	<10	<1	43
30	D96-413	45	<0.2	1.87	245	35	<5	4.51	<1	26	121	136	6.00	<10	1.73	1117	5	0.02	32	1900	36	<5	<20	53	0.03	<10	118	<10	<1	112
31	D96-414	50	<0.2	1.64	25	30	<5	4.39	<1	20	110	77	4.13	<10	1.62	966	2	0.02	28	1690	28	5	<20	51	0.04	<10	116	<10	<1	123

QC/DATA:

Resplit:

R/S 1	D96-384	505	0.4	0.91	385	30	5	0.43	<1	40	87	42	9.40	<10	0.52	326	13	<0.01	36	920	24	<5	<20	8	<0.01	<10	28	<10	<1	13
-------	---------	-----	-----	------	-----	----	---	------	----	----	----	----	------	-----	------	-----	----	-------	----	-----	----	----	-----	---	-------	-----	----	-----	----	----


Repeat:

1	D96-384	555	0.6	1.06	405	40	10	0.47	<1	48	88	44	>10	<10	0.53	349	11	<0.01	42	990	26	<5	<20	6	<0.01	<10	28	<10	<1	15
10	D96-393	100	<0.2	1.73	35	100	<5	3.06	<1	14	71	47	4.36	<10	0.99	942	13	<0.01	14	1310	28	<5	<20	53	<0.01	<10	52	<10	<1	40
19	D96-402	-	>30	2.47	130	45	<5	0.50	<1	74	74	>10000	>10	<10	1.64	769	99	<0.01	26	3120	22	<5	<20	6	0.12	<10	251	<10	<1	88

Standard:

GEO'96		150	1.0	1.75	60	150	<5	1.86	<1	15	56	80	3.80	<10	0.97	680	<1	<0.01	20	650	20	<5	<20	58	0.09	<10	76	<10	7	72
--------	--	-----	-----	------	----	-----	----	------	----	----	----	----	------	-----	------	-----	----	-------	----	-----	----	----	-----	----	------	-----	----	-----	---	----

df/5302
XLS/96Teuton#7


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (250) 573-5700
Fax (250) 573-4557

CERTIFICATE OF ASSAY AS 96-5337

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

9-Oct-96

ATTENTION: DINO CREMONESE

No. of samples received: 12

Sample type: ROCK

PROJECT: # CLONE

SHIPMENT: # S96-53

P.O. #: NONE GIVEN

Samples submitted by: R.MCLEOD

ET #.	Tag #	Au (g/t)	Au (oz/t)
2	RJM96-050	12.94	0.377
3	RJM96-051	28.03	0.817
4	RJM96-052	1.36	0.040
6	RJM96-054	4.42	0.129
7	RJM96-055	35.33	1.030
9	RJM96-057	18.97	0.553
10	RJM96-058	193.40	5.640
11	RJM96-059	67.28	1.962

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

XLS/96Teuton#11

Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5337

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557


ATTENTION: DINO CREMONESE

No. of samples received: 12
Sample type: ROCK
PROJECT: # CLONE
SHIPMENT: # S96-53
P.O. #: NONE GIVEN
Samples submitted by: R.MCLEOD

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
1	RJM96-049	10	<0.2	2.26	10	65	10	0.79	<1	233	18	64	6.31	<10	2.07	1007	3	0.01	10	2440	10	<5	<20	17	0.14	<10	101	<10	7	113	
2	RJM96-050	>1000	0.6	2.19	40	75	5	1.04	<1	440	30	139	8.58	<10	2.06	1123	8	<0.01	16	1820	10	<5	<20	17	0.12	<10	136	<10	<1	154	
3	RJM96-051	>1000	1.0	1.22	125	85	25	0.55	<1	372	31	104	>10	<10	0.90	613	21	<0.01	15	1230	8	<5	<20	17	0.11	<10	185	<10	<1	97	
4	RJM96-052	>1000	1.4	3.38	50	80	<5	1.11	2	142	28	1100	8.40	<10	3.42	1500	12	<0.01	13	2250	12	<5	<20	23	0.11	<10	158	<10	<1	102	
5	RJM96-053	60	<0.2	2.50	10	155	5	0.66	<1	44	24	43	6.79	<10	2.22	1912	2	<0.01	14	2250	14	5	<20	16	0.11	<10	101	<10	<1	320	
6	RJM96-054	>1000	<0.2	1.70	20	135	<5	0.50	<1	84	32	114	>10	<10	1.37	2031	9	<0.01	12	1500	20	10	<20	14	0.08	<10	167	<10	<1	513	
7	RJM96-055	>1000	2.8	1.01	80	135	5	0.58	<1	47	29	194	>10	<10	0.45	886	16	<0.01	4	1560	60	15	<20	14	0.07	<10	189	<10	<1	363	
8	RJM96-056	105	<0.2	2.80	10	90	<5	0.58	<1	53	20	239	7.73	<10	2.68	1574	3	<0.01	15	2060	16	10	<20	12	0.12	<10	116	<10	1	254	
9	RJM96-057	>1000	2.6	2.17	80	120	<5	0.58	3	324	42	1019	>10	<10	1.98	1781	10	<0.01	21	1710	24	<5	<20	16	0.08	<10	166	<10	<1	394	
10	RJM96-058	>1000	9.0	0.67	145	110	15	0.40	1	57	<1	211	>10	<10	0.27	490	41	<0.01	8	920	52	10	<20	11	0.05	<10	165	<10	<1	124	
11	RJM96-059	>1000	3.0	0.41	145	100	35	0.46	<1	23	24	78	>10	<10	0.07	220	50	<0.01	3	1410	76	<5	<20	15	0.06	<10	177	<10	<1	55	
12	RJM96-061	530	4.0	2.28	70	115	<5	0.70	2	139	20	2461	6.83	<10	1.95	1264	5	<0.01	15	2220	16	15	<20	16	0.09	<10	110	<10	1	321	
QC/DATA:																															
Resplit:																															
1	RJM96-049	10	<0.2	2.35	15	65	10	0.82	<1	243	25	71	6.70	<10	2.15	1056	4	0.01	9	2540	10	<5	<20	16	0.14	<10	106	<10	7	120	
Repeat:																															
1	RJM96-049	10	<0.2	2.34	15	70	10	0.83	<1	241	18	66	6.55	<10	2.13	1047	2	0.02	9	2530	12	<5	<20	16	0.14	<10	105	<10	7	119	
10	RJM96-058	>1000	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Standard:																															
GEO'96		-	1.2	1.73	65	160	<5	1.73	<1	18	59	71	3.94	<10	0.95	690	<1	0.01	22	700	18	<5	<20	59	0.11	<10	75	<10	5	70	

dl/5337
XLS/96Teuton#11
Fax to Dino Vancouver 604-682-3992


per
ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5343

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

1-Oct-96

ATTENTION: DINO CREMONESE

No. of samples received: 26
Sample Type: ROCK
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
P.O.#: NONE GIVEN
Samples submitted by: NOT INDICATED

ET #.	Tag #	Au (g/t)	Au (oz/t)	As (%)	Co (%)
10	ERK96-253	-	-	-	0.045
11	ERK96-254	2.14	0.062	3.40	0.181
13	ERK96-256	1.39	0.041	-	-
19	ERK96-262	5.27	0.154	1.05	0.088
20	ERK96-263	1.25	0.036	-	0.020
21	ERK96-264	1.87	0.055	-	0.064
23	ERK96-266	1.41	0.041	-	-
24	ERK96-267	13.34	0.389	1.90	0.120
25	ERK96-268	14.01	0.409	3.22	0.255

QC DATA:

Standard:

CD-I	-	-	0.66	-
SUI-a	-	-	-	0.042

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

XLS/96Teuton#10
fax @: 604-682-3992/D.Cremonese

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5343

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 26

Sample Type: ROCK

PROJECT #: NONE GIVEN

SHIPMENT #: NONE GIVEN

P.O.#: NONE GIVEN

Samples submitted by: NOT INDICATED

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	A96-590	70	<0.2	3.16	945	75	<5	7.37	<1	113	24	118	7.80	<10	2.70	1397	5	0.03	7	1860	10	<5	<20	117	0.02	<10	169	<10	<1	59
2	A96-591	5	<0.2	3.84	10	140	5	6.11	<1	30	6	63	8.35	<10	2.98	1125	5	0.01	6	1980	6	<5	<20	89	0.01	<10	117	<10	<1	58
3	A96-592	5	<0.2	3.19	<5	175	<5	6.07	<1	26	22	119	7.71	<10	1.93	983	5	<0.01	10	1620	20	<5	<20	72	0.01	<10	89	<10	<1	61
4	A96-593	5	<0.2	1.70	<5	315	<5	6.51	<1	14	17	40	3.85	<10	0.64	908	3	<0.01	5	1050	12	<5	<20	59	<0.01	<10	36	<10	<1	43
5	A96-594	10	0.4	3.41	50	100	<5	5.78	<1	33	16	135	8.75	<10	2.08	1431	9	<0.01	6	1730	12	<5	<20	67	<0.01	<10	87	<10	<1	84
6	A96-595	5	0.6	3.02	80	80	<5	>10	<1	48	16	329	>10	<10	1.75	1748	10	<0.01	11	2130	22	<5	<20	143	<0.01	<10	89	<10	<1	92
7	A96-596	5	<0.2	4.14	20	115	<5	>10	<1	39	44	108	>10	<10	2.78	1894	7	<0.01	16	2010	20	<5	<20	96	0.01	<10	147	<10	<1	89
8	A96-597	5	<0.2	3.48	35	275	5	>10	1	27	41	48	8.83	<10	1.96	2041	13	<0.01	10	1800	16	<5	<20	118	<0.01	<10	120	<10	<1	125
9	A96-598	10	0.4	3.06	135	165	<5	>10	1	31	27	72	8.09	<10	1.67	2278	10	<0.01	16	1880	24	<5	<20	97	<0.01	<10	97	<10	<1	143
10	ERK96-253	275	<0.2	3.06	6765	75	<5	0.67	<1	480	32	87	8.45	<10	2.48	1017	26	0.02	5	2700	16	5	<20	11	0.01	<10	216	<10	<1	54
11	ERK96-254	>1000	1.6	2.49	>10000	75	<5	0.42	<1	1964	24	224	>10	<10	1.77	857	40	<0.01	<1	1560	24	75	<20	9	0.01	<10	180	<10	<1	46
12	ERK96-255	60	<0.2	3.93	585	60	<5	0.82	<1	51	12	195	>10	<10	3.07	1483	9	0.02	6	2400	12	<5	<20	9	0.17	<10	360	<10	<1	65
13	ERK96-256	>1000	0.6	3.35	2980	90	<5	0.49	<1	69	12	365	>10	<10	2.11	1144	26	0.01	8	1870	34	<5	<20	8	0.10	<10	295	<10	<1	76
14	ERK96-257	50	<0.2	4.23	355	65	<5	1.06	<1	45	15	221	>10	<10	3.30	1550	8	0.02	6	2550	12	<5	<20	12	0.25	<10	362	<10	<1	58
15	ERK96-258	135	<0.2	4.20	740	70	<5	0.76	<1	38	12	177	>10	<10	3.49	1645	12	0.02	9	2700	12	<5	<20	11	0.07	<10	352	<10	<1	66
16	ERK96-259	5	<0.2	4.39	85	70	<5	0.73	<1	35	11	99	>10	<10	3.96	1815	11	0.02	10	2900	10	<5	<20	13	0.07	<10	351	<10	<1	80
17	ERK96-260	5	<0.2	3.55	80	55	<5	3.78	<1	45	10	175	>10	<10	3.43	1669	6	0.02	8	2460	10	<5	<20	29	0.17	<10	291	<10	<1	70
18	ERK96-261	5	<0.2	4.17	40	75	<5	1.44	<1	47	10	144	>10	<10	3.83	2085	6	0.02	9	2860	12	<5	<20	19	0.18	<10	326	<10	2	92
19	ERK96-262	>1000	1.6	2.07	>10000	70	<5	1.68	<1	978	14	228	8.53	<10	1.06	1116	20	<0.01	7	2320	26	<5	<20	17	0.05	<10	83	<10	1	87
20	ERK96-263	>1000	0.6	2.34	1715	85	<5	1.40	<1	204	18	158	7.39	<10	1.32	831	18	<0.01	6	1710	16	<5	<20	15	0.07	<10	89	<10	<1	76

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
21	ERK96-264	>1000	1.4	2.80	7185	90	<5	0.51	<1	738	27	262	>10	<10	1.70	1142	23	0.01	5	1830	24	<5	<20	7	0.06	<10	152	<10	<1	89
22	ERK96-265	250	0.8	2.22	360	80	<5	1.51	<1	115	31	232	7.69	<10	1.42	1066	32	<0.01	10	1840	20	<5	<20	16	0.06	<10	138	<10	1	95
23	ERK96-266	>1000	1.6	2.23	1045	80	<5	1.15	<1	118	18	216	7.15	<10	1.05	749	22	<0.01	14	3090	24	<5	<20	13	0.09	<10	99	<10	8	86
24	ERK96-267	>1000	4.6	2.65	>10000	70	<5	0.49	<1	1329	13	729	>10	<10	1.39	692	84	<0.01	1	1680	46	<5	<20	6	0.04	<10	109	<10	<1	106
25	ERK96-268	>1000	4.6	3.15	>10000	65	<5	0.33	<1	2379	8	891	>10	<10	2.01	880	54	<0.01	<1	1220	60	<5	<20	4	0.04	<10	163	<10	<1	103
26	ERK96-269	205	<0.2	2.19	910	55	<5	1.80	<1	103	40	79	5.35	<10	1.84	1005	4	0.02	7	1850	10	<5	<20	18	0.06	<10	172	<10	2	70

QC/DATA:**Resplit:**

1	A96-590	75	<0.2	3.27	995	80	<5	7.58	<1	125	24	122	7.86	<10	2.78	1453	7	0.02	8	2190	14	<5	<20	116	0.02	<10	187	<10	<1	63
---	---------	----	------	------	-----	----	----	------	----	-----	----	-----	------	-----	------	------	---	------	---	------	----	----	-----	-----	------	-----	-----	-----	----	----

Repeat:

1	A96-590	45	<0.2	3.42	980	80	<5	7.52	<1	119	26	122	7.95	<10	2.89	1364	8	0.03	10	1890	14	<5	<20	117	0.02	<10	195	<10	<1	66
10	ERK96-253	265	0.2	3.17	7380	75	<5	0.70	<1	508	33	88	8.88	<10	2.58	1070	28	0.02	6	2790	14	15	<20	12	0.01	<10	225	<10	<1	56
19	ERK96-262	>1000	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-


Standard:

GEO'96		140	1.0	1.93	60	155	<5	2.37	<1	24	72	70	4.18	<10	1.00	745	<1	0.02	24	810	26	<5	<20	55	0.16	<10	86	<10	6	82
--------	--	-----	-----	------	----	-----	----	------	----	----	----	----	------	-----	------	-----	----	------	----	-----	----	----	-----	----	------	-----	----	-----	---	----

df/5343
 XLS/96Teuton#10
 fax @: 604-682-3992/D.Cremonese


 ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5361

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

2-Oct-96

ATTENTION: DINO CREMONESE

No. of samples received: 72
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-56
P.O.#: NONE GIVEN
Samples submitted by: MILO WOODWARD

ET #.	Tag #	Au (g/t)	Au (oz/t)	Co (%)
17	TP96-017	-	-	0.028
23	TP96-023	1.32	0.038	-
55	TP96-055	-	-	0.057
64	TP96-064	-	-	0.043
68	TP96-068	1.75	0.051	0.026

QC/DATA:

Standard				
Su1a	-	-	-	0.042


ECO-TECH LABORATORIES LTD.

per Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/96Teuton#10
Fax @: 604-682-3992/D.Cremonese

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5361

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 72

Sample Type: ROCK

PROJECT #: CLONE

SHIPMENT #: S96-56

P.O.#: NONE GIVEN

Samples submitted by: MILO WOODWARD

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	TP96-001	5	0.4	2.92	35	90	5	4.93	1	15	13	32	6.51	<10	1.77	1919	5	<0.01	5	1490	24	<5	<20	79	<0.01	<10	51	<10	<1	166
2	TP96-002	5	1.0	1.81	25	90	<5	6.03	3	13	16	59	4.60	<10	1.56	2512	5	<0.01	4	1120	56	<5	<20	82	<0.01	<10	48	<10	<1	218
3	TP96-003	10	1.2	2.27	90	120	<5	5.87	9	19	10	89	6.43	<10	1.38	3252	5	<0.01	5	1270	68	<5	<20	52	<0.01	<10	78	<10	<1	683
4	TP96-004	5	1.8	2.00	50	60	<5	9.54	4	20	15	61	5.46	<10	1.72	3720	5	<0.01	7	1070	86	<5	<20	146	<0.01	<10	62	<10	<1	268
5	TP96-005	15	1.0	1.97	445	80	<5	5.17	<1	13	16	29	4.55	<10	1.17	2652	5	<0.01	2	1200	52	<5	<20	74	<0.01	<10	32	<10	<1	144
6	TP96-006	5	<0.2	3.35	15	50	5	6.62	8	26	20	53	8.51	<10	1.89	1599	17	<0.01	7	1670	54	<5	<20	131	<0.01	<10	186	<10	<1	373
7	TP96-007	5	<0.2	2.91	20	50	<5	7.69	5	23	17	75	7.00	<10	1.77	1591	13	<0.01	7	1370	46	<5	<20	152	<0.01	<10	141	<10	<1	268
8	TP96-008	5	0.4	2.43	15	100	<5	5.08	<1	19	18	80	5.03	<10	1.41	1455	4	<0.01	8	1890	26	<5	<20	79	<0.01	<10	63	<10	<1	86
9	TP96-009	140	0.6	3.15	485	40	<5	2.24	<1	28	47	132	>10	<10	2.41	904	10	<0.01	10	1340	58	<5	<20	34	<0.01	<10	170	<10	<1	150
10	TP96-010	20	0.4	3.15	30	45	<5	5.85	<1	28	34	92	7.47	<10	2.53	1353	5	<0.01	9	1340	28	<5	<20	98	<0.01	<10	138	<10	<1	87
11	TP96-011	5	<0.2	2.13	25	95	<5	7.22	<1	19	15	49	4.42	<10	1.16	1265	3	<0.01	6	1820	16	<5	<20	107	<0.01	<10	53	<10	<1	55
12	TP96-012	10	<0.2	2.47	35	80	<5	6.78	<1	25	16	54	5.20	<10	1.20	1181	3	0.01	7	2020	16	<5	<20	104	<0.01	<10	61	<10	<1	52
13	TP96-013	30	0.6	1.53	20	90	<5	7.61	<1	15	28	63	3.47	<10	1.12	1567	8	<0.01	19	1180	20	<5	<20	149	<0.01	<10	54	<10	2	86
14	TP96-014	10	0.2	2.81	20	90	<5	>10	<1	23	18	91	5.69	<10	2.15	1886	4	<0.01	9	1590	14	<5	<20	234	<0.01	<10	81	<10	<1	68
15	TP96-015	5	<0.2	3.36	5	95	<5	8.42	<1	22	12	74	6.06	<10	3.02	1642	4	<0.01	8	1780	14	<5	<20	206	<0.01	<10	110	<10	<1	53
16	TP96-016	25	<0.2	4.17	30	70	<5	6.30	<1	29	12	55	7.97	<10	3.69	1369	6	0.01	9	1830	18	<5	<20	152	0.02	<10	155	<10	<1	66
17	TP96-017	360	0.4	3.63	1685	50	<5	4.22	<1	212	11	709	>10	<10	3.33	948	8	<0.01	9	1910	30	<5	<20	107	0.01	20	147	<10	<1	48
18	TP96-018	10	<0.2	3.77	<5	105	<5	6.90	<1	26	33	64	6.10	<10	4.31	1396	3	<0.01	11	1300	20	<5	<20	184	0.01	<10	190	<10	<1	84
19	TP96-019	25	<0.2	4.42	25	55	<5	5.66	<1	31	34	110	7.71	<10	4.54	1315	4	<0.01	14	1540	24	<5	<20	195	0.01	<10	198	<10	<1	106
20	TP96-020	20	<0.2	3.58	20	65	<5	5.71	<1	32	25	72	6.60	<10	3.62	1352	4	<0.01	10	1530	24	<5	<20	142	0.01	<10	152	<10	<1	61
21	TP96-021	10	<0.2	4.07	35	50	<5	5.84	<1	35	27	55	7.27	<10	4.21	1523	4	<0.01	12	1730	22	<5	<20	156	0.02	<10	203	<10	<1	66
22	TP96-022	240	0.6	1.78	125	60	<5	>10	<1	24	22	67	4.80	<10	1.36	2126	4	<0.01	5	1140	14	<5	<20	331	<0.01	<10	62	<10	<1	71
23	TP96-023	>1000	4.4	2.38	535	45	<5	1.94	<1	115	12	2330	>10	<10	1.39	571	14	<0.01	15	640	122	<5	<20	37	<0.01	20	55	<10	<1	77
24	TP96-024	40	0.4	3.87	70	65	<5	5.92	<1	34	43	107	7.95	<10	3.11	1629	6	<0.01	16	1470	24	<5	<20	106	<0.01	<10	133	<10	<1	92
25	TP96-025	60	0.2	3.58	45	70	<5	4.73	<1	32	29	103	8.12	<10	2.28	1146	7	<0.01	15	2020	30	<5	<20	84	<0.01	<10	105	<10	<1	113

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	BI	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	TP96-026	65	0.2	3.39	75	70	<5	4.86	<1	34	20	108	7.53	<10	2.47	1284	6	<0.01	16	1900	34	<5	<20	96	<0.01	<10	117	<10	<1	161
27	TP96-027	20	<0.2	3.44	10	75	<5	5.53	<1	29	31	79	6.29	<10	3.42	1469	3	<0.01	11	1870	24	<5	<20	114	0.02	<10	144	<10	<1	104
28	TP96-028	25	<0.2	3.85	20	110	<5	4.08	<1	26	16	65	7.11	<10	3.90	1310	4	0.01	9	1940	26	<5	<20	85	0.02	<10	191	<10	<1	89
29	TP96-029	35	<0.2	3.62	25	45	<5	3.86	<1	31	18	120	7.18	<10	3.67	1108	4	<0.01	9	2080	26	<5	<20	97	0.01	<10	178	<10	<1	81
30	TP96-030	10	0.2	3.19	20	40	<5	5.17	<1	35	27	197	7.58	<10	2.94	1216	5	<0.01	11	1680	26	<5	<20	129	0.01	<10	167	<10	<1	68
31	TP96-031	40	<0.2	3.21	25	55	<5	3.24	<1	13	1	53	6.97	<10	3.02	962	2	0.01	5	1940	26	<5	<20	58	0.08	<10	194	<10	<1	37
32	TP96-032	50	<0.2	2.51	120	40	<5	5.84	<1	18	12	156	6.85	<10	2.17	1041	4	0.01	9	1810	22	<5	<20	99	0.02	<10	171	<10	<1	43
33	TP96-033	35	<0.2	3.24	30	60	<5	3.84	<1	15	5	97	7.29	<10	2.88	976	3	0.01	6	1840	24	<5	<20	71	0.05	<10	205	<10	<1	40
34	TP96-034	120	<0.2	4.05	235	45	<5	4.52	<1	34	43	101	8.96	<10	3.81	1128	10	0.01	14	1870	32	<5	<20	109	0.02	<10	245	<10	<1	54
35	TP96-035	175	<0.2	3.66	145	45	<5	3.10	<1	44	36	231	9.30	<10	3.30	834	9	0.02	12	1730	30	<5	<20	107	0.01	<10	237	<10	<1	43
36	TP96-036	95	<0.2	3.63	90	50	<5	3.17	<1	36	44	164	8.56	<10	3.57	849	6	0.02	11	1860	24	<5	<20	77	0.02	<10	220	<10	<1	37
37	TP96-037	35	0.6	1.00	50	60	<5	>10	<1	11	9	44	2.04	<10	0.51	2846	1	<0.01	4	1220	12	<5	<20	149	<0.01	<10	21	<10	13	33
38	TP96-038	40	0.2	1.42	50	85	<5	4.68	<1	14	14	60	2.85	<10	0.87	1037	2	0.02	2	1810	16	<5	<20	77	0.02	<10	39	<10	3	43
39	TP96-039	50	<0.2	2.16	15	90	<5	4.09	<1	20	16	136	4.92	<10	1.63	1101	3	0.02	5	1750	18	<5	<20	94	0.06	<10	88	<10	1	46
40	TP96-040	10	<0.2	2.33	5	485	<5	5.29	<1	13	42	30	4.40	<10	1.96	1348	2	0.01	15	1750	14	<5	<20	124	0.02	<10	78	<10	2	49
41	TP96-041	45	0.4	2.06	55	220	<5	6.07	<1	21	34	31	4.15	<10	1.58	1707	3	<0.01	10	1570	24	<5	<20	88	<0.01	<10	63	<10	5	59
42	TP96-042	90	<0.2	3.36	20	95	<5	3.62	<1	32	17	174	7.66	<10	2.72	1375	3	0.01	14	1890	22	<5	<20	64	0.10	<10	151	<10	<1	74
43	TP96-043	45	<0.2	4.14	30	80	<5	4.10	<1	31	20	193	>10	<10	3.65	1751	8	0.01	13	1440	22	<5	<20	76	0.13	<10	247	<10	<1	89
44	TP96-044	30	0.2	0.81	15	605	<5	6.32	<1	33	8	125	3.53	<10	0.28	930	1	<0.01	5	1900	12	<5	<20	138	0.04	<10	34	<10	4	104
45	TP96-045	25	0.8	0.76	10	40	<5	5.54	6	11	7	301	2.88	<10	0.32	1319	3	<0.01	2	1630	42	<5	<20	107	0.01	<10	22	<10	2	275
46	TP96-046	10	2.6	1.66	20	35	<5	8.61	6	16	14	86	6.29	<10	0.99	2394	9	<0.01	3	810	134	<5	<20	142	<0.01	<10	37	<10	<1	420
47	TP96-047	35	1.2	1.68	55	25	<5	5.27	<1	16	14	61	6.12	<10	1.14	1381	6	<0.01	7	1240	40	<5	<20	85	<0.01	<10	53	<10	<1	68
48	TP96-048	5	0.8	0.59	5	160	<5	3.07	<1	8	9	190	2.27	<10	0.22	499	1	0.01	1	1830	10	<5	<20	62	0.03	<10	25	<10	3	35
49	TP96-049	5	0.8	0.71	25	275	<5	3.56	<1	8	10	378	2.39	<10	0.28	650	1	<0.01	3	1710	16	<5	<20	62	0.02	<10	25	<10	3	36
50	TP96-050	10	1.2	1.84	20	55	<5	9.06	<1	16	15	66	5.47	<10	1.13	2205	7	<0.01	6	1120	66	<5	<20	145	<0.01	<10	48	<10	<1	144
51	TP96-051	10	3.0	1.11	60	40	<5	6.95	10	21	11	70	5.58	<10	0.42	2117	17	<0.01	5	1230	142	<5	<20	89	<0.01	<10	27	<10	<1	631
52	TP96-052	20	2.2	2.06	60	35	<5	5.41	1	15	18	54	7.04	<10	1.18	1776	7	<0.01	7	1120	74	<5	<20	70	<0.01	<10	59	<10	<1	195
53	TP96-053	40	2.0	1.82	140	165	<5	3.88	9	29	12	134	4.75	<10	0.93	2165	8	<0.01	5	1550	76	<5	<20	51	<0.01	<10	43	<10	7	318
54	TP96-054	60	1.0	1.60	120	85	<5	1.59	<1	171	10	188	3.61	<10	0.93	1171	2	0.01	1	2090	26	<5	<20	26	<0.01	<10	35	<10	3	119
55	TP96-055	615	1.4	1.81	525	65	<5	3.19	<1	510	10	243	4.26	<10	1.19	1216	3	0.01	<1	1830	30	<5	<20	42	0.02	<10	46	<10	2	74
56	TP96-056	5	<0.2	0.56	45	35	<5	4.03	<1	15	8	52	4.16	<10	0.12	549	3	<0.01	3	1740	10	<5	<20	115	0.03	<10	23	<10	2	45
57	TP96-057	5	<0.2	1.00	105	60	<5	1.91	<1	12	9	28	3.89	<10	0.51	464	3	0.01	2	1640	14	<5	<20	61	0.04	<10	21	<10	<1	51
58	TP96-058	15	0.2	1.63	80	40	<5	1.16	<1	13	8	30	4.49	<10	1.14	673	3	0.01	2	1980	24	<5	<20	74	0.03	<10	30	<10	<1	53
59	TP96-059	5	<0.2	1.35	20	285	<5	1.92	<1	9	9	22	2.59	<10	0.90	682	<1	0.01	2	2040	16	<5	<20	42	0.04	<10	28	<10	3	30
60	TP96-060	5	<0.2	1.42	10	110	<5	1.98	<1	11	13	129	2.90	<10	0.99	650	1	0.02	2	2020	16	<5	<20	42	0.04	<10	39	<10	<1	39

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
61	TP96-061	35	0.2	1.22	35	125	<5	3.98	<1	11	12	94	2.63	<10	0.68	788	1	0.01	2	1850	14	<5	<20	54	0.04	<10	25	<10	4	33
62	TP96-062	40	0.8	1.29	25	95	<5	3.41	<1	20	11	92	2.95	<10	0.74	775	2	0.01	2	1900	20	<5	<20	44	0.03	<10	24	<10	3	37
63	TP96-063	30	1.0	1.26	40	65	<5	4.41	<1	28	8	103	2.90	<10	0.72	918	4	<0.01	2	1840	22	<5	<20	60	0.02	<10	31	<10	5	47
64	TP96-064	250	3.0	2.01	325	75	<5	5.53	<1	349	12	1278	4.62	<10	1.34	1782	3	<0.01	5	1900	26	<5	<20	79	0.04	<10	67	<10	2	187
65	TP96-065	165	0.6	1.96	110	75	<5	3.13	<1	163	10	419	4.39	<10	1.29	1101	3	0.01	4	2130	62	<5	<20	48	0.04	<10	73	<10	3	109
66	TP96-066	10	0.4	1.79	15	110	<5	1.00	<1	17	8	76	3.67	<10	1.30	724	2	0.02	<1	2000	34	<5	<20	17	0.01	<10	43	<10	1	40
67	TP96-067	45	0.8	1.22	40	45	<5	4.09	3	16	15	143	3.47	<10	0.69	894	4	0.01	1	1810	22	<5	<20	65	0.04	<10	49	<10	1	86
68	TP96-068	>1000	3.4	1.40	255	45	<5	2.91	<1	208	14	1471	4.33	<10	0.87	834	5	<0.01	1	1970	18	<5	<20	46	0.03	<10	43	<10	<1	103
69	TP96-069	375	1.4	1.56	75	45	<5	3.11	<1	39	15	590	3.37	<10	1.16	883	2	<0.01	1	1840	16	<5	<20	47	0.04	<10	45	<10	<1	80
70	TP96-070	40	1.6	1.40	70	40	<5	3.01	<1	41	11	774	2.95	<10	1.05	803	<1	0.01	1	1900	16	<5	<20	46	0.04	<10	41	<10	2	58
71	TP96-071	10	<0.2	3.12	15	45	<5	5.31	<1	30	12	108	6.48	<10	2.69	1316	2	0.02	7	2070	18	<5	<20	79	0.11	<10	189	<10	<1	63
72	TP96-072	30	<0.2	2.71	30	35	<5	5.59	<1	31	22	184	7.00	<10	2.48	1329	4	0.02	11	1780	18	<5	<20	92	0.12	<10	211	<10	<1	59
73	TP96-073	80	<0.2	3.51	45	60	<5	2.52	<1	45	14	271	8.99	<10	3.08	1408	5	0.02	13	2260	24	<5	<20	38	0.15	<10	267	<10	<1	56

QC/DATA:

Resplit:

R/S 1	TP96-001	10	0.6	2.89	35	85	5	4.67	<1	13	12	28	6.47	<10	1.74	1763	5	<0.01	4	1410	26	<5	<20	75	<0.01	<10	45	<10	<1	167
R/S 36	TP96-036	70	<0.2	3.71	100	55	<5	3.43	<1	38	45	162	8.93	<10	3.64	906	6	0.02	12	1920	24	<5	<20	84	0.02	<10	224	<10	<1	38
R/S 71	TP96-071	5	<0.2	3.12	20	50	<5	5.31	<1	31	12	106	6.56	<10	2.69	1315	2	0.02	7	2140	22	<5	<20	77	0.13	<10	191	<10	1	66

Repeat:

1	TP96-001	10	0.6	2.81	40	85	<5	4.86	<1	14	21	30	6.48	<10	1.73	1895	5	<0.01	5	1530	28	<5	<20	77	<0.01	<10	49	<10	<1	170
10	TP96-010	20	0.2	2.98	30	50	<5	5.74	<1	26	30	88	6.80	<10	2.41	1323	5	<0.01	9	1200	30	<5	<20	86	<0.01	<10	122	<10	<1	83
19	TP96-019	35	<0.2	4.31	30	50	<5	5.54	<1	31	33	111	7.58	<10	4.42	1292	4	<0.01	14	1560	26	<5	<20	191	0.01	<10	193	<10	<1	103
36	TP96-036	50	<0.2	3.56	85	50	<5	3.14	<1	36	43	166	8.45	<10	3.49	834	5	0.02	10	1860	32	<5	<20	77	0.02	<10	216	<10	<1	37
45	TP96-045	15	1.0	0.78	5	50	<5	5.63	6	11	7	305	2.91	<10	0.32	1338	3	<0.01	2	1680	44	<5	<20	113	0.02	<10	23	<10	3	276
54	TP96-054	70	1.0	1.64	125	85	<5	1.58	<1	171	10	188	3.62	<10	0.94	1177	2	<0.01	2	2080	24	<5	<20	24	0.01	<10	36	<10	3	116
71	TP96-071	5	<0.2	3.08	25	50	<5	5.34	<1	30	12	105	6.52	<10	2.67	1319	2	0.02	7	2110	20	<5	<20	78	0.11	<10	188	<10	<1	65

Standard:

GEO'96	145	1.0	1.85	66	120	<5	1.82	<1	17	65	76	3.70	<10	0.94	689	<1	0.01	21	760	24	<5	<20	56	0.10	<10	67	<10	2	69	
GEO'96	145	1.2	1.84	60	155	<5	1.85	<1	20	65	76	4.21	<10	0.98	716	<1	0.02	23	780	24	<5	<20	58	0.12	<10	80	<10	3	65	
GEO'96	150	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

[Signature]
ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5362

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

2-Oct-96

ATTENTION: DINO CREMONESE


No. of samples received: 7
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-57
P.O.#: NONE GIVEN
Samples submitted by: MILO WOODWARD

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	MM96-064	1.76	0.051

QC/DATA:

Resplit:
R/S 1 MM96-064 1.33 0.039

XLS/96Teuton#10
Fax @: 604-682-3992/D.Cremonese


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

2-Oct-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5362

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 7
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-57
P.O.#: NONE GIVEN
Samples submitted by: MILO WOODWARD

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	MM96-064	>1000	5.0	3.11	85	40	<5	0.33	<1	73	16	1226	>10	<10	2.25	889	26	<0.01	5	1290	136	<5	<20	8	<0.01	<10	105	<10	<1	82
2	MM96-065	465	2.2	2.89	155	90	<5	0.46	<1	25	5	83	>10	<10	1.34	400	8	<0.01	6	1510	14	<5	<20	13	0.01	20	83	<10	<1	68
3	MM96-066	420	5.0	3.77	200	60	<5	0.23	<1	45	23	215	>10	<10	1.77	413	16	<0.01	7	950	20	<5	<20	5	<0.01	30	160	<10	<1	70
4	MM96-067	30	2.2	2.71	105	40	<5	0.65	15	47	20	163	>10	<10	1.97	929	13	<0.01	9	1360	38	<5	<20	12	<0.01	<10	151	<10	<1	746
5	MM96-068	15	1.2	1.50	80	55	5	4.45	<1	15	9	10	6.40	<10	0.52	1484	9	<0.01	1	1300	16	<5	<20	53	<0.01	<10	27	<10	1	22
6	MM96-069	270	2.2	3.60	180	60	25	0.43	<1	90	13	81	>10	<10	2.02	2030	24	<0.01	5	1090	94	<5	<20	8	<0.01	<10	127	<10	<1	96
7	MM96-070	155	9.0	3.08	95	45	<5	0.41	<1	39	11	519	>10	<10	2.15	842	12	<0.01	7	1780	132	<5	<20	10	<0.01	<10	193	<10	<1	110

QC/DATA:

Resplit:

R/S 1 MM96-064 >1000


Repeat:

1	MM96-064	>1000	5.2	2.86	90	35	<5	0.32	<1	72	15	1205	>10	<10	2.06	854	25	<0.01	6	1300	144	<5	<20	10	<0.01	<10	98	<10	<1	86
---	----------	-------	-----	------	----	----	----	------	----	----	----	------	-----	-----	------	-----	----	-------	---	------	-----	----	-----	----	-------	-----	----	-----	----	----

Standard:

GEO'96 150

df/1156
XLS/96Teuton#10
Fax @: 604-682-3992/D.Cremonese



ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AS 96-5367

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

30-Sep-96

ATTENTION: DINO CREMONESE

No. of samples received: 21
Sample Type: Saw Cut
PROJECT #: Clone
SHIPMENT #: S96-58
P.O.#: None Given
Samples submitted by: Milo Woodward

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	SC-96-6-001	2.49	0.073
2	SC-96-6-002	3.34	0.097
3	SC-96-7-001	2.03	0.059
4	SC-96-7-002	5.33	0.155
5	SC-96-8-001	1.52	0.044
7	SC-96-9-002	11.24	0.328
8	SC-96-10-001	18.04	0.526
9	SC-96-10-002	3.02	0.088
12	SC-96-12-001	2.91	0.085
13	SC-96-12-002	2.23	0.065
14	SC-96-13-001	3.29	0.096
17	SC-96-14-002	2.52	0.073

QC/DATA:

Resplit:

R/S 1 SC-96-6-001 2.43 0.071

ECO-TECH LABORATORIES LTD.

per Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/96Teuton#9
Fax @: 604-682-3992/D.Cremonese

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5367

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 21

Sample Type: Saw Cut.

PROJECT #: Clone

SHIPMENT #: S96-58

P.O.#: None Given

Samples submitted by: Milo Woodward

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	SC-96-6-001	>1000	0.4	2.23	20	95	<5	4.10	<1	9	34	56	4.86	10	1.85	1191	8	0.02	3	1690	46	<5	<20	66	0.03	<10	119	<10	<1	76
2	SC-96-6-002	>1000	0.6	1.87	15	60	<5	4.06	<1	10	30	46	3.92	<10	1.50	911	9	0.02	4	1720	36	<5	<20	67	0.03	<10	102	<10	<1	58
3	SC-96-7-001	>1000	0.8	2.16	10	75	<5	1.95	<1	7	33	88	4.89	<10	1.55	893	6	0.02	5	1930	22	<5	<20	41	0.01	<10	95	<10	<1	62
4	SC-96-7-002	>1000	1.0	3.20	10	65	<5	2.94	<1	9	26	126	7.22	<10	2.59	1118	16	0.01	3	1760	46	<5	<20	56	0.01	<10	146	<10	<1	93
5	SC-96-8-001	>1000	0.2	2.03	5	65	<5	3.82	<1	7	28	49	4.70	<10	1.42	977	3	0.02	4	1700	18	<5	<20	101	0.01	<10	86	<10	<1	62
6	SC-96-9-001	60	<0.2	3.55	<5	110	10	4.17	<1	22	4	8	6.87	<10	2.98	1162	4	0.01	7	2520	18	<5	<20	84	0.03	<10	106	<10	<1	78
7	SC-96-9-002	>1000	2.4	2.51	5	115	<5	3.06	<1	29	17	178	6.08	<10	1.80	849	42	<0.01	7	1310	22	<5	<20	74	0.03	<10	77	<10	<1	83
8	SC-96-10-001	>1000	4.2	2.68	10	115	<5	1.53	<1	36	13	281	7.43	<10	1.92	797	35	<0.01	9	1770	26	<5	<20	37	0.02	<10	90	<10	<1	92
9	SC-96-10-002	>1000	0.6	2.16	<5	130	<5	3.45	<1	11	22	49	4.21	20	1.46	1064	4	0.01	3	1850	18	<5	<20	81	0.02	<10	64	<10	1	85
10	SC-96-11-001	15	<0.2	1.85	<5	410	<5	3.59	<1	10	14	10	2.72	<10	1.41	946	1	<0.01	6	1840	18	<5	<20	93	0.01	<10	39	<10	2	50
11	SC-96-11-002	215	0.4	2.20	10	440	<5	4.53	<1	40	13	63	4.41	<10	1.71	1054	3	<0.01	6	1810	16	<5	<20	119	0.02	<10	55	<10	<1	58
12	SC-96-12-001	>1000	<0.2	3.55	<5	60	<5	4.00	<1	47	65	164	8.43	<10	4.17	1297	<1	0.01	15	2180	20	<5	<20	51	0.14	<10	230	<10	<1	44
13	SC-96-12-002	>1000	<0.2	3.44	<5	80	10	2.34	<1	54	18	54	9.33	<10	3.84	1314	4	0.01	6	2680	18	<5	<20	35	0.11	<10	227	<10	<1	38
14	SC-96-13-001	>1000	<0.2	4.12	<5	70	20	2.23	<1	46	34	20	9.97	<10	4.78	1327	3	<0.01	10	2170	16	<5	<20	30	0.12	<10	174	<10	<1	41
15	SC-96-13-002	45	<0.2	3.40	<5	70	<5	2.54	<1	29	37	231	8.74	<10	3.79	1223	3	0.01	12	2800	22	<5	<20	31	0.11	<10	215	<10	<1	38
16	SC-96-14-001	5	<0.2	2.98	10	75	<5	3.65	<1	29	52	153	7.25	<10	3.38	1092	<1	0.02	11	2140	22	<5	<20	40	0.15	<10	178	<10	<1	34
17	SC-96-14-002	>1000	<0.2	3.41	<5	640	15	1.88	<1	42	18	24	9.47	<10	3.83	1183	4	<0.01	6	2470	22	<5	<20	40	0.10	<10	190	<10	<1	33
18	A96-016	10	0.6	2.55	<5	165	<5	4.80	<1	26	31	376	5.29	<10	2.05	2068	4	<0.01	19	2050	16	<5	<20	57	<0.01	<10	76	<10	1	19
19	A96-017	5	0.4	1.26	<5	470	<5	5.56	<1	4	26	205	2.28	<10	0.85	809	2	0.01	5	2110	8	5	<20	77	<0.01	<10	23	<10	2	11
20	A96-018	5	0.2	1.05	<5	315	<5	9.10	<1	9	42	90	2.25	<10	0.94	1304	1	<0.01	8	1170	6	<5	<20	127	<0.01	<10	35	<10	4	14
21	A96-019	5	5.8	3.21	<5	65	<5	5.74	111	23	84	356	6.14	<10	2.76	1309	3	<0.01	16	1770	2006	<5	<20	204	0.02	<10	170	<10	<1	4208

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
QC/DATA:																															
<i>Resplit:</i>																															
R/S 1	SC-96-6-001	>1000	0.6	2.16	20	90	<5	4.42	<1	9	36	52	4.70	10	1.78	1191	8	0.02	3	1710	46	<5	<20	68	0.03	<10	114	<10	<1	78	
<i>Repeat:</i>																															
1	SC-96-6-001	>1000	0.6	2.23	20	90	<5	4.06	<1	9	33	54	4.83	10	1.82	1177	8	0.02	2	1680	48	<5	<20	65	0.03	<10	119	<10	<1	75	
10	SC-96-11-001	10	<0.2	1.99	<5	445	<5	3.64	<1	10	14	10	2.77	<10	1.48	970	<1	<0.01	5	1870	14	<5	<20	95	0.01	<10	43	<10	2	50	
19	A96-017	5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
<i>Standard:</i>																															
GEO'96		150	1.2	1.92	65	145	<5	1.93	<1	20	67	71	4.33	<10	1.01	741	<1	0.02	24	78	22	<5	<20	62	0.12	<10	82	<10	3	67	

dl/5361
 XLS/96Teuton#10
 Fax @: 604-682-3992/D.Cremonese

per

 ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (250) 573-5700
Fax (250) 573-4557

CERTIFICATE OF ASSAY AS 96-5368

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

4-Oct-96

ATTENTION: DINO CREMONESE

No. of samples received: 9
Sample type: CORE
PROJECT: # NONE GIVEN
SHIPMENT: # NONE GIVEN
P.O. #: NONE GIVEN
Samples submitted by: NOT INDICATED

ET #.	Tag #	Au (g/t)	Au (oz/t)
8	96-SC-8	3.99	0.116

XLS/96Teuton#11
fax@682-3992/d.cremonese

per 
ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

4-Oct-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5368

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 9
Sample Type: CORE
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
P. O. #: NONE GIVEN
Samples submitted by: NOT INDICATED

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	96-SC-1	10	<0.2	3.72	15	65	<5	2.48	<1	45	21	327	>10	<10	3.15	1108	9	0.02	9	1430	16	<5	<20	48	0.06	<10	218	<10	<1	52
2	96-SC-2	25	<0.2	3.71	10	55	<5	3.49	<1	38	25	226	9.24	<10	3.22	1273	10	0.01	10	1420	12	<5	<20	65	0.04	<10	214	<10	<1	49
3	96-SC-3	20	<0.2	3.78	50	65	<5	2.87	<1	45	18	222	8.50	<10	3.32	1332	5	<0.01	9	1770	14	<5	<20	55	0.04	<10	182	<10	<1	74
4	96-SC-4	160	<0.2	2.97	10	60	<5	3.04	<1	50	19	137	6.93	<10	2.15	873	3	0.01	9	1520	10	<5	<20	68	0.05	<10	137	<10	<1	46
5	96-SC-5	250	<0.2	2.69	<5	45	<5	3.56	<1	27	15	287	6.92	<10	1.98	882	4	0.02	8	1810	14	<5	<20	69	0.05	<10	156	<10	<1	43
6	96-SC-6	690	<0.2	2.94	<5	60	10	2.55	<1	56	19	67	8.58	<10	2.05	715	3	<0.01	11	1360	14	<5	<20	50	0.07	<10	186	<10	<1	47
7	96-SC-7	480	<0.2	2.66	25	50	<5	3.07	<1	68	14	598	6.59	<10	1.97	753	3	0.01	7	1670	12	<5	<20	57	0.05	<10	158	<10	<1	41
8	96-SC-8	>1000	0.4	1.97	70	55	<5	2.92	<1	86	20	355	5.31	<10	1.51	859	3	0.01	5	1380	12	<5	<20	58	0.01	<10	119	<10	<1	151
9	96-SC-9	155	<0.2	3.07	<5	55	<5	2.74	<1	34	16	175	7.87	<10	2.39	872	3	0.01	10	1480	12	<5	<20	58	0.07	<10	153	<10	<1	47

QC/DATA:

Resplit:

1	96-SC-1	15	<0.2	3.82	20	65	<5	2.52	<1	47	20	336	>10	<10	3.21	1190	9	0.02	10	1550	20	<5	<20	52	0.07	<10	224	<10	<1	56
---	---------	----	------	------	----	----	----	------	----	----	----	-----	-----	-----	------	------	---	------	----	------	----	----	-----	----	------	-----	-----	-----	----	----


Repeat:

1	96-SC-1	-	<0.2	3.69	15	65	<5	2.53	<1	46	22	317	>10	<10	3.08	1120	8	0.02	10	1510	18	<5	<20	47	0.07	<10	218	<10	<1	54
---	---------	---	------	------	----	----	----	------	----	----	----	-----	-----	-----	------	------	---	------	----	------	----	----	-----	----	------	-----	-----	-----	----	----

Standard:

GEO 96		140	1.0	1.71	70	160	<5	1.90	<1	18	60	69	3.90	<10	0.96	663	<1	0.02	20	690	20	<5	<20	55	0.12	<10	77	<10	4	72
--------	--	-----	-----	------	----	-----	----	------	----	----	----	----	------	-----	------	-----	----	------	----	-----	----	----	-----	----	------	-----	----	-----	---	----

df/5368
XLS/96Teuton#10
fax@682.3992/d.cremonese


ECO-TECH LABORATORIES LTD.
per Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (250) 573-5700
Fax (250) 573-4557

CERTIFICATE OF ASSAY AS 96-5371

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

4-Oct-96

ATTENTION: DINO CREMONESE

No. of samples received: 59
Sample Type: ROCK
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
P.O.#: NONE GIVEN
Samples submitted by: NOT INDICATED


ET #.	Tag #	Au (g/t)	Au (oz/t)	Co (%)
2	96-TP-75	1.85	0.054	-
3	96-TP-76	-	-	0.030
4	96-TP-77	-	-	0.032
5	96-TP-78	-	-	0.062
13	96-TP-86	-	-	0.038

QC/DATA:

Standard:

Su-1a - - 0.041

XLS/96Teuton#9
fax@682-3992/d.cremonese


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

4-Oct-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5371

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received:59
Sample Type:ROCK
PROJECT #:NONE GIVEN
SHIPMENT #:NONE GIVEN
P.O.#: NONE GIVEN
Samples submitted by:NOT INDICATED

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	96-TP-74	75	1.0	2.46	50	120	<5	5.05	<1	18	17	59	5.31	<10	1.60	1586	4	<0.01	5	1270	16	<5	<20	112	<0.01	<10	40	<10	<1	45
2	96-TP-75	>1000	4.4	3.36	2945	70	<5	3.03	<1	140	15	269	>10	<10	2.48	1143	8	<0.01	5	1280	54	<5	<20	70	<0.01	<10	103	<10	<1	45
3	96-TP-76	925	4.6	3.03	1765	75	<5	3.19	<1	237	14	838	>10	<10	2.12	945	9	<0.01	2	1250	44	<5	<20	109	<0.01	<10	88	<10	<1	46
4	96-TP-77	745	3.6	3.12	2965	70	<5	8.80	<1	262	10	361	8.75	<10	2.54	1918	8	<0.01	4	1180	26	<5	<20	142	0.02	<10	161	<10	8	42
5	96-TP-78	555	3.0	4.12	6190	80	<5	1.86	<1	550	8	241	>10	<10	3.38	1022	13	<0.01	6	1520	32	<5	<20	44	0.02	<10	233	<10	<1	65
6	96-TP-79	270	1.0	4.34	375	75	<5	1.48	<1	52	8	302	>10	<10	3.77	611	15	<0.01	8	1770	22	<5	<20	36	0.02	<10	242	<10	<1	64
7	96-TP-80	230	0.8	4.41	125	75	<5	3.92	<1	22	9	182	>10	<10	3.98	1012	7	<0.01	9	1620	18	<5	<20	70	0.03	<10	244	<10	<1	50
8	96-TP-81	480	3.2	4.33	2890	75	<5	4.17	<1	155	19	281	>10	<10	3.98	1122	11	<0.01	11	1610	32	<5	<20	96	0.02	<10	272	<10	<1	37
9	96-TP-82	530	3.4	4.62	440	85	<5	2.44	<1	73	8	402	>10	<10	4.10	811	9	<0.01	11	1620	32	<5	<20	51	0.02	<10	258	<10	<1	43
10	96-TP-83	145	<0.2	4.61	195	90	<5	1.62	<1	34	7	194	>10	<10	4.10	679	8	<0.01	10	1820	18	<5	<20	44	0.02	<10	257	<10	<1	39
11	96-TP-84	20	<0.2	4.66	80	90	<5	0.99	<1	19	5	142	>10	<10	4.43	550	7	<0.01	9	1730	18	<5	<20	24	0.03	<10	261	<10	<1	40
12	96-TP-85	70	0.2	4.68	80	80	<5	1.87	<1	20	6	125	>10	<10	4.37	649	6	<0.01	7	1600	20	<5	<20	51	0.02	<10	231	<10	<1	45
13	96-TP-86	490	5.2	4.53	3925	70	<5	0.45	<1	320	12	653	>10	<10	3.96	586	11	<0.01	9	1330	54	<5	<20	10	0.02	20	235	<10	<1	49
14	96-TP-87	175	5.0	4.53	685	80	<5	0.57	<1	86	7	905	>10	<10	3.83	495	10	<0.01	6	1710	48	<5	<20	10	0.02	10	236	<10	<1	55
15	96-TP-88	95	4.4	3.91	295	95	<5	2.47	<1	48	14	767	9.86	<10	3.26	889	7	<0.01	4	1690	34	<5	<20	61	0.02	<10	204	<10	<1	55
16	96-TP-89	140	2.2	2.82	80	100	<5	1.47	<1	33	14	431	7.49	<10	1.93	1285	16	<0.01	4	1460	26	<5	<20	30	<0.01	<10	60	<10	<1	73
17	96-TP-90	135	1.2	2.52	75	110	<5	3.28	6	36	17	106	6.27	<10	1.68	1116	16	<0.01	7	1490	48	<5	<20	92	<0.01	<10	60	<10	<1	139
18	96-TP-91	130	<0.2	3.65	<5	235	10	1.77	<1	27	8	15	7.98	<10	2.32	990	6	<0.01	5	1940	14	<5	<20	45	<0.01	<10	85	<10	<1	95
19	96-TP-95	520	3.2	3.37	205	80	15	1.94	1	52	24	88	>10	<10	2.07	2500	13	<0.01	4	1050	144	<5	<20	33	<0.01	<10	116	<10	<1	186
20	96-TP-97	105	0.6	2.87	10	90	<5	2.83	1	34	16	76	7.16	<10	2.26	1738	4	0.01	6	1390	32	<5	<20	53	0.01	<10	127	<10	<1	82
21	96-TP-98	265	2.4	2.20	65	105	<5	5.61	<1	18	18	161	5.24	<10	2.01	1310	4	0.01	4	1270	36	<5	<20	97	<0.01	<10	101	<10	1	60
22	96-TP-105	180	0.8	2.83	15	115	<5	3.18	15	20	30	139	7.27	<10	2.16	1184	6	0.01	9	1620	36	<5	<20	111	<0.01	<10	153	<10	<1	142
23	96-TP-106	20	0.6	2.86	15	130	<5	4.40	1	16	27	116	6.63	<10	2.02	974	5	0.02	11	1520	32	<5	<20	165	<0.01	<10	152	<10	<1	82
24	96-TP-109	155	<0.2	3.31	<5	150	<5	3.35	<1	19	30	19	6.33	<10	2.61	1270	5	0.01	8	1390	20	<5	<20	45	<0.01	<10	105	<10	<1	120
25	96-TP-110	165	0.4	2.60	30	65	<5	1.90	<1	84	27	110	7.85	<10	1.94	1369	6	<0.01	8	1340	28	<5	<20	27	<0.01	<10	108	<10	<1	112

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	96-TP-111	75	0.2	2.29	30	75	<5	3.47	<1	51	19	105	5.74	<10	1.91	1235	5	<0.01	4	1320	24	<5	<20	49	<0.01	<10	103	<10	<1	57
27	96-TP-112	360	1.2	1.86	45	80	10	7.69	<1	68	18	36	7.35	<10	1.23	1984	6	<0.01	3	980	66	<5	<20	74	<0.01	<10	70	<10	2	52
28	96-TP-113	15	<0.2	2.08	<5	60	10	3.54	<1	47	17	4	6.03	<10	1.59	1066	6	<0.01	5	1240	20	<5	<20	53	<0.01	<10	105	<10	<1	60
29	96-TP-114	45	<0.2	2.52	5	110	5	3.91	<1	37	20	7	5.34	<10	1.84	1192	2	<0.01	3	1240	20	<5	<20	82	<0.01	<10	110	<10	<1	94
30	96-TP-115	180	<0.2	2.75	10	145	<5	3.20	<1	25	24	26	5.47	<10	2.00	1082	3	<0.01	5	1260	18	<5	<20	47	<0.01	<10	101	<10	<1	107
31	96-TP-116	25	<0.2	2.30	<5	110	<5	4.09	<1	26	29	3	4.87	<10	1.63	1117	3	0.01	6	1210	14	<5	<20	63	<0.01	<10	99	<10	<1	79
32	96-TP-117	780	1.2	2.45	90	70	<5	2.95	<1	66	31	335	7.70	<10	1.80	1395	7	<0.01	10	1310	38	<5	<20	45	<0.01	<10	107	<10	<1	79
33	96-TP-118	470	0.6	2.04	15	85	<5	4.83	<1	36	17	82	4.88	<10	1.51	1276	4	<0.01	2	1270	30	<5	<20	85	<0.01	<10	84	<10	<1	48
34	96-TP-119	195	<0.2	3.67	<5	100	10	1.54	<1	23	21	24	8.13	<10	2.83	1288	5	0.02	8	1350	26	<5	<20	25	<0.01	<10	133	<10	<1	164
35	96-TP-120	70	<0.2	2.91	<5	70	10	2.82	<1	29	13	10	7.85	<10	2.48	1240	5	0.01	5	1300	20	<5	<20	49	0.01	<10	124	<10	<1	69
36	96-TP-121	10	<0.2	3.11	<5	110	5	2.99	<1	17	13	3	6.28	<10	2.47	1270	4	0.01	5	1230	16	<5	<20	61	0.02	<10	113	<10	<1	66
37	96-TP-122	10	<0.2	3.21	<5	100	<5	2.91	<1	14	22	25	6.38	<10	2.68	1056	4	0.02	5	1170	16	<5	<20	58	0.03	<10	113	<10	<1	67
38	96-TP-123	10	0.8	2.78	85	80	<5	4.97	9	44	29	136	6.46	<10	2.29	1495	4	<0.01	7	1390	42	<5	<20	88	<0.01	<10	149	<10	<1	600
39	96-TP-124	375	2.2	2.59	190	75	15	3.12	2	112	29	119	>10	<10	2.17	1521	23	<0.01	13	1080	110	<5	<20	55	<0.01	<10	147	<10	<1	183
40	96-TP-125	5	0.8	2.56	50	65	<5	4.11	3	21	30	181	5.99	<10	2.24	1222	4	<0.01	6	1330	52	<5	<20	63	<0.01	<10	140	<10	<1	222
41	96-TP-126	120	0.6	2.82	35	90	5	2.95	3	88	33	153	8.96	<10	1.67	1791	33	<0.01	8	1290	44	<5	<20	38	<0.01	<10	122	<10	<1	171
42	96-TP-127	150	1.0	3.12	20	100	<5	4.55	1	70	16	168	9.45	<10	1.79	1861	10	<0.01	9	1190	58	<5	<20	72	<0.01	<10	131	<10	<1	131
43	96-TP-128	30	<0.2	2.36	20	105	<5	6.02	1	13	11	34	5.56	<10	1.40	1290	3	<0.01	3	1060	36	<5	<20	83	<0.01	<10	98	<10	3	140
44	96-TP-129	10	<0.2	2.43	<5	145	5	4.79	2	17	9	47	5.36	<10	1.46	1233	4	0.01	2	1090	92	<5	<20	115	<0.01	<10	96	<10	<1	227
45	96-TP-130	10	<0.2	2.49	<5	90	5	3.98	2	42	32	18	7.33	<10	1.69	1743	8	<0.01	10	1240	94	<5	<20	75	<0.01	<10	93	<10	<1	204
46	96-TP-131	35	0.4	2.11	20	70	5	4.06	18	45	27	46	7.84	<10	1.36	2225	5	<0.01	12	1100	52	<5	<20	90	<0.01	<10	89	<10	<1	634
47	96-TP-132	10	1.0	2.40	45	80	<5	0.66	<1	34	25	541	6.71	<10	1.13	758	7	<0.01	14	1510	22	<5	<20	11	<0.01	<10	87	<10	<1	181
48	96-TP-133	65	0.4	3.36	65	110	5	0.66	<1	30	31	73	9.06	<10	1.53	915	10	<0.01	9	1270	36	<5	<20	18	<0.01	<10	114	<10	<1	196
49	96-TP-134	5	0.4	2.75	95	95	10	0.95	<1	24	24	39	7.87	<10	1.25	702	9	<0.01	7	1080	44	<5	<20	22	<0.01	<10	67	<10	<1	130
50	96-TP-135	5	0.6	2.16	50	100	<5	2.66	<1	17	18	93	5.65	<10	1.10	1002	7	<0.01	5	1000	32	<5	<20	54	<0.01	<10	58	<10	<1	130
51	96-TP-136	280	1.2	3.01	1255	50	<5	2.93	<1	116	21	775	8.09	<10	2.85	940	6	<0.01	7	1590	22	<5	<20	51	0.02	<10	209	<10	<1	52
52	96-TP-137	90	0.6	3.01	355	55	<5	5.99	<1	46	18	332	8.45	<10	2.67	1304	8	<0.01	6	1430	16	<5	<20	76	0.02	<10	171	<10	<1	51
53	96-TP-138	10	0.2	2.44	30	75	<5	3.82	<1	9	20	63	5.91	<10	2.20	910	4	<0.01	6	1460	18	<5	<20	69	0.01	<10	138	<10	<1	45
54	96-TP-139	75	1.4	2.45	50	60	<5	4.24	<1	20	25	272	8.16	<10	1.80	1013	7	<0.01	8	1510	26	<5	<20	57	0.01	<10	176	<10	<1	50
55	96-TP-140	20	1.8	2.33	40	55	<5	3.28	<1	32	31	354	8.18	<10	1.77	1111	6	0.01	11	1570	28	<5	<20	45	0.01	<10	201	<10	<1	49
56	96-TP-141	10	1.0	2.90	70	70	<5	4.09	<1	15	21	87	5.61	<10	3.17	1310	4	0.01	7	1530	26	5	<20	95	<0.01	<10	185	<10	<1	57
57	96-TP-142	10	0.6	2.25	35	50	<5	5.06	<1	17	24	121	5.67	<10	2.11	1157	5	<0.01	6	1410	26	<5	<20	80	<0.01	<10	155	<10	<1	42
58	96-TP-143	55	1.8	2.25	70	55	<5	3.66	<1	20	27	161	5.81	<10	2.22	927	6	<0.01	10	1590	32	<5	<20	55	<0.01	<10	142	<10	<1	39
59	96-TP-144	310	9.8	3.34	230	65	<5	1.85	<1	57	22	1087	>10	<10	2.99	830	71	<0.01	10	1150	94	<5	<20	41	0.01	<10	169	<10	<1	63

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC/DATA:																														
<i>Resplit:</i>																														
1	96-TP-74	60	1.0	2.30	60	110	<5	5.34	<1	20	14	52	5.31	<10	1.51	1671	4	<0.01	4	1300	20	<5	<20	112	<0.01	<10	39	<10	<1	48
36	96-TP-121	20	<0.2	3.10	<5	110	5	2.99	<1	17	16	3	6.53	<10	2.47	1312	4	0.01	4	1310	20	<5	<20	58	0.02	<10	115	<10	<1	74
<i>Repeat:</i>																														
1	96-TP-74	50	1.0	2.61	50	135	<5	5.41	<1	20	16	60	5.68	<10	1.67	1689	4	<0.01	5	1370	18	<5	<20	117	<0.01	<10	43	<10	<1	50
10	96-TP-83	155	<0.2	4.58	200	85	<5	1.61	<1	35	7	193	>10	<10	4.08	673	8	<0.01	9	1810	18	<5	<20	46	0.02	10	255	<10	<1	38
19	96-TP-95	430	3.8	3.34	200	85	25	2.14	3	50	24	86	>10	<10	2.05	2472	17	<0.01	6	1010	146	<5	<20	37	<0.01	<10	116	<10	<1	189
31	96-TP-116	25	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
36	96-TP-121	-	<0.2	3.25	<5	125	10	3.12	<1	18	14	3	6.55	<10	2.53	1314	4	0.02	5	1340	22	<5	<20	62	0.02	<10	118	<10	<1	71
40	96-TP-125	5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
45	96-TP-130	-	0.4	2.41	<5	90	10	3.85	2	41	31	17	7.12	<10	1.64	1690	6	<0.01	8	1210	92	<5	<20	74	<0.01	<10	90	<10	<1	199
49	96-TP-134	5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
58	96-TP-143	50	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
<i>Standard:</i>																														
GEO'96		140	1.2	1.74	60	170	<5	1.76	<1	18	64	70	3.96	<10	0.98	694	<1	0.01	23	740	26	<5	<20	54	0.10	<10	73	<10	6	64
GEO'96		145	1.2	1.80	65	165	<5	1.90	<1	18	65	75	3.80	<10	0.90	648	<1	0.01	22	740	22	<5	<20	56	0.10	<10	72	<10	5	72

df/5371
 XLS/96Teuton#10
 fax@682-3992/d.cremonese

per
 ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (250) 573-5700
Fax (250) 573-4557

CERTIFICATE OF ASSAY AS 96-5398

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

8-Oct-96

ATTENTION: DINO CREMONESE

No. of samples received: 30
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: S96-60
P.O.#: NONE GIVEN
Samples submitted by: THEODORE PETERS

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	96TP-145	2.22	0.065
2	96TP-146	2.48	0.072
3	96TP-147	2.96	0.086
11	96TP-155	2.71	0.079
12	96TP-156	2.82	0.082
13	96TP-157	3.72	0.108

QC/DATA:

Resplit:

R/S 1 96TP-145 2.32 0.068

XLS/96Teuton#11
Fax to Dino Vancouver 604-682-3992


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

8-Oct-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5398

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received:30
Sample Type:ROCK
PROJECT #:CLONE
SHIPMENT #:S96-60
P.O.#: NONE GIVEN
Samples submitted by:THEODORE PETERS

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	96TP-145	>1000	1.8	4.83	720	75	<5	1.85	<1	96	24	547	>10	<10	4.58	939	9	<0.01	9	1710	20	<5	<20	36	0.03	<10	316	<10	<1	49
2	96TP-146	>1000	0.4	4.92	680	80	<5	4.23	<1	70	36	204	>10	<10	4.51	1272	8	<0.01	7	1600	14	<5	<20	73	0.02	<10	295	<10	<1	46
3	96TP-147	>1000	2.8	3.73	2300	50	<5	3.38	<1	188	35	599	>10	<10	3.30	1133	10	<0.01	10	840	22	<5	<20	62	0.02	<10	196	<10	<1	39
4	96TP-148	335	4.0	5.27	220	65	<5	2.87	<1	36	20	660	>10	<10	4.79	1329	10	<0.01	9	1630	22	<5	<20	49	0.03	<10	267	<10	<1	57
5	96TP-149	80	1.4	4.35	200	70	<5	1.41	<1	30	14	229	9.29	<10	3.93	1070	7	<0.01	5	1640	28	<5	<20	28	0.01	<10	162	<10	<1	68
6	96TP-150	40	1.0	2.53	115	75	<5	2.96	<1	19	18	136	6.28	<10	2.30	799	5	<0.01	3	1550	16	<5	<20	60	0.01	<10	128	<10	<1	42
7	96TP-151	215	1.6	2.87	2435	100	<5	2.12	<1	107	13	411	6.52	<10	2.65	846	6	<0.01	3	1450	20	5	<20	41	<0.01	<10	113	<10	<1	56
8	96TP-152	130	6.2	1.81	240	80	<5	2.96	<1	29	13	3095	5.32	<10	1.51	763	4	<0.01	3	1450	28	<5	<20	66	<0.01	<10	81	<10	<1	60
9	96TP-153	100	2.2	4.98	740	75	<5	0.92	<1	65	21	156	9.95	<10	5.04	976	7	<0.01	9	1890	34	<5	<20	14	0.02	<10	250	<10	<1	63
10	96TP-154	840	12.2	4.02	3155	65	<5	0.43	<1	221	14	1004	>10	<10	3.25	758	18	<0.01	7	1460	52	<5	<20	12	0.02	<10	210	<10	<1	65
11	96TP-155	>1000	10.4	5.24	8395	65	<5	1.11	<1	544	3	574	>10	<10	3.92	2179	16	<0.01	5	1290	82	<5	<20	25	0.01	<10	222	<10	<1	131
12	96TP-156	>1000	9.8	4.00	8590	60	<5	1.65	<1	686	7	745	>10	<10	3.03	1571	13	<0.01	8	1260	58	<5	<20	59	0.01	<10	170	<10	<1	89
13	96TP-157	>1000	8.8	3.34	5250	60	<5	2.99	<1	518	8	726	>10	<10	2.63	1461	11	<0.01	9	1170	44	<5	<20	77	0.01	<10	135	<10	<1	78
14	96TP-158	70	3.2	1.99	225	80	<5	3.66	<1	27	11	182	5.21	<10	1.69	881	7	<0.01	3	1640	32	<5	<20	72	<0.01	<10	77	<10	1	41
15	96TP-159	80	4.4	2.24	390	100	<5	2.54	<1	36	11	260	5.74	<10	1.74	817	5	<0.01	3	1800	26	5	<20	54	<0.01	<10	83	<10	<1	67
16	96TP-160	115	3.8	3.17	225	105	<5	1.30	<1	38	13	213	7.98	<10	2.31	667	5	<0.01	4	1880	40	<5	<20	29	0.01	<10	115	<10	<1	75
17	96TP-161	285	4.4	2.97	400	85	<5	3.14	<1	63	11	272	8.26	<10	2.40	918	8	<0.01	5	1560	58	<5	<20	63	0.01	<10	128	<10	<1	73
18	96TP-162	640	11.6	2.29	6225	85	<5	6.71	<1	211	11	408	6.57	<10	1.83	1532	6	<0.01	1	1300	48	15	<20	92	<0.01	<10	70	<10	<1	50
19	96TP-163	40	3.6	3.64	60	50	<5	3.63	<1	32	29	152	7.30	<10	3.81	1310	4	0.01	7	1880	38	<5	<20	67	0.01	<10	247	<10	<1	45
20	96TP-164	55	5.2	3.91	75	65	<5	2.99	<1	43	32	177	8.54	<10	4.10	1298	6	0.01	9	1980	30	<5	<20	57	0.01	<10	284	<10	<1	46

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
21	96TP-165	5	1.6	4.29	50	70	<5	1.64	<1	31	35	99	7.66	<10	5.12	971	11	0.01	9	2090	24	<5	<20	32	0.02	<10	274	<10	<1	51
22	96TP-166	5	1.6	4.46	25	60	<5	1.43	<1	29	18	155	8.49	<10	5.14	940	36	<0.01	8	2160	24	<5	<20	39	0.02	<10	278	<10	<1	52
23	96TP-167	10	0.4	5.22	25	55	15	1.90	<1	21	22	77	>10	<10	4.87	1222	9	<0.01	8	2060	20	<5	<20	49	0.02	<10	262	<10	<1	50
24	96TP-168	15	1.2	3.66	70	55	<5	3.75	<1	27	32	268	8.56	<10	3.51	1088	6	<0.01	14	1690	14	<5	<20	88	0.03	<10	231	<10	<1	33
25	96TP-169	100	1.4	3.00	135	50	<5	7.27	<1	24	20	346	9.41	<10	2.73	1296	6	<0.01	10	1430	10	<5	<20	143	0.02	<10	198	<10	<1	27
26	96TP-170	200	3.2	3.45	310	60	<5	5.47	<1	57	19	1355	>10	<10	2.61	1292	14	<0.01	15	1200	16	<5	<20	103	0.02	<10	182	<10	<1	37
27	96TP-171	800	3.6	3.40	2490	35	<5	4.84	<1	200	23	796	>10	<10	3.17	1331	15	<0.01	18	1230	26	<5	<20	68	0.02	<10	211	30	<1	35
28	96TP-172	25	0.4	3.51	85	65	<5	2.69	<1	22	25	173	7.42	<10	3.73	1200	6	<0.01	7	1880	24	<5	<20	65	0.02	<10	235	<10	<1	44
29	96TP-173	60	1.4	3.84	90	75	<5	2.82	<1	39	26	116	7.14	<10	4.24	1192	5	<0.01	10	1920	32	<5	<20	99	0.02	<10	264	<10	<1	57
30	96TP-174	20	1.2	3.51	55	85	<5	3.09	<1	24	26	159	6.65	<10	3.94	1174	5	0.01	6	1980	24	<5	<20	49	0.02	<10	258	<10	<1	59

QC/DATA:

Resplit:

1	96TP-145	>1000	1.8	4.64	635	70	<5	1.85	<1	83	23	517	>10	<10	4.38	912	9	<0.01	10	1760	28	<5	<20	36	0.02	<10	304	<10	<1	49
---	----------	-------	-----	------	-----	----	----	------	----	----	----	-----	-----	-----	------	-----	---	-------	----	------	----	----	-----	----	------	-----	-----	-----	----	----

Repeat:

1	96TP-145	>1000	2.0	4.80	820	80	<5	1.87	<1	107	24	531	>10	<10	4.53	943	8	<0.01	9	1800	26	<5	<20	34	0.03	<10	315	<10	<1	50
10	96TP-154	775	12.8	4.16	3410	75	<5	0.44	<1	233	13	1037	>10	<10	3.38	771	16	<0.01	5	1470	50	<5	<20	17	0.02	20	216	<10	<1	64
19	96TP-163	-	3.0	3.41	55	35	<5	3.45	<1	30	27	135	6.94	<10	3.58	1242	5	<0.01	7	1850	34	<5	<20	54	<0.01	<10	233	<10	<1	44
20	96TP-164	50	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

Standard:

GEO'96		145	1.0	1.77	65	150	<5	1.77	<1	19	61	70	4.02	<10	0.95	678	<1	0.02	21	730	24	<5	<20	52	0.12	<10	79	<10	4	70
--------	--	-----	-----	------	----	-----	----	------	----	----	----	----	------	-----	------	-----	----	------	----	-----	----	----	-----	----	------	-----	----	-----	---	----

df/5398
 XLS/96Teuton#11
 fax@682-3992/d.cremonese


 ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (250) 573-5700
Fax (250) 573-4557

CERTIFICATE OF ASSAY AS 96-5399

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2


9-Oct-96

ATTENTION: DINO CREMONESE

No. of samples received: 9
Sample type: ROCK
PROJECT: # CLONE
SHIPMENT: # S96-61
P.O. #: NONE GIVEN
Samples submitted by: DALE ROBERTS

ET #.	Tag #	Au (g/t)	Au (oz/t)
2	SC-16-001	3.39	0.099
7	SC18-1	3.47	0.101

XLS/96Teuton#11
Fax to Dino Vancouver 604-682-3992


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

9-Oct-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5399

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 9
Sample type: ROCK
PROJECT: # CLONE
SHIPMENT: # S96-61
P.O. # NONE GIVEN
Samples submitted by: DALE ROBERTS

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	SC-15-001	105	<0.2	3.37	15	55	<5	2.10	1	52	32	1331	>10	<10	2.87	972	<1	<0.01	11	1660	26	<5	20	21	0.26	<10	245	<10	2	58
2	SC-16-001	>1000	<0.2	3.10	65	45	<5	4.27	<1	79	74	360	9.07	<10	3.21	1215	<1	<0.01	11	1700	20	<5	<20	41	0.20	<10	249	<10	<1	58
3	SC-16-002	750	<0.2	3.00	25	55	<5	3.68	<1	32	58	112	6.74	<10	3.15	1075	<1	0.03	15	1810	22	<5	<20	43	0.23	<10	201	<10	<1	36
4	SC-17-001	145	<0.2	3.06	35	50	<5	3.15	<1	54	7	240	>10	<10	2.97	1126	2	<0.01	7	1870	18	<5	20	39	0.22	<10	229	<10	<1	51
5	SC-17-002	10	<0.2	3.27	40	60	20	3.08	<1	36	46	60	9.77	<10	3.27	1257	<1	0.01	14	1940	22	<5	<20	37	0.24	<10	250	<10	<1	41
6	SC-17-003	40	<0.2	3.27	40	70	<5	1.00	<1	43	28	253	>10	<10	2.86	1225	4	<0.01	11	1990	24	<5	20	22	0.23	<10	238	<10	<1	30
7	SC-18-1	>1000	<0.2	3.00	15	60	<5	3.26	1	45	71	232	8.93	<10	3.14	1259	<1	<0.01	11	1920	24	<5	<20	43	0.19	<10	232	<10	<1	64
8	SC-18-2	170	<0.2	3.23	5	45	20	4.64	<1	29	15	52	8.18	<10	3.11	1341	<1	<0.01	9	1950	24	<5	<20	51	0.20	<10	212	<10	<1	68
9	SC-18-3	35	<0.2	3.15	25	45	10	4.04	<1	44	7	36	8.16	<10	2.86	1287	<1	<0.01	7	2170	22	<5	<20	50	0.19	<10	207	<10	<1	80

QC/DATA:

Resplit:																															
1	SC-15-001	85	<0.2	3.50	25	55	<5	2.09	<1	52	28	1277	>10	<10	2.76	1004	<1	<0.01	13	1710	26	<5	40	21	0.26	<10	250	<10	<1	58	
Repeat:																															
1	SC-15-001	-	<0.2	3.37	20	55	<5	2.06	<1	52	31	1326	>10	<10	2.65	974	<1	<0.01	13	1660	26	<5	20	22	0.25	<10	243	<10	<1	62	
Standard:																															
GEO 96		150	0.8	1.84	65	160	<5	1.92	<1	20	68	80	4.31	<10	0.95	714	<1	0.02	25	780	20	<5	<20	58	0.14	<10	82	<10	5	67	

df/5391
XLS/96Teuton#11
Fax to Dino Vancouver 604-682-3992


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer



ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (250) 573-5700
Fax (250) 573-4557

CERTIFICATE OF ASSAY AS 96-5401

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2


9-Oct-96

ATTENTION: DINO CREMONESE

No. of samples received: 60
Sample Type: rock
PROJECT #: clone
SHIPMENT #: s96-62
P.O.#: none given
Samples submitted by: A. Raven

ET #.	Tag #	Au (g/t)	Au (oz/t)
24	ERK96-293	2.32	0.068
47	ERK96-316	2.09	0.061

XLS/96Teuton#11
Fax to Dino Vancouver 604-682-3992

per 
ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AS-5401

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 60

Sample Type: rock -

PROJECT #: clone

SHIPMENT #: s96-62

P.O.#: none given

Samples submitted by: A.Raven

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	ERK96-270	5	7.8	3.30	165	85	85	1.74	2	25	21	94	9.73	<10	2.00	1800	13	<0.01	5	1050	148	<5	20	24	<0.01	<10	116	<10	<1	265
2	ERK96-271	5	0.6	2.61	40	125	10	5.15	<1	15	23	47	5.61	<10	1.73	2082	5	0.01	5	1100	24	<5	<20	63	<0.01	<10	78	<10	<1	66
3	ERK96-272	5	1.0	2.75	60	145	5	5.78	2	17	24	88	5.86	<10	1.57	1735	5	<0.01	8	1250	40	<5	<20	161	0.01	<10	73	<10	<1	81
4	ERK96-273	10	1.0	2.57	20	225	<5	3.17	5	16	27	200	5.28	<10	1.13	1024	5	<0.01	8	1320	128	<5	<20	94	<0.01	<10	66	<10	<1	344
5	ERK96-274	5	0.6	2.47	5	105	<5	2.09	2	25	19	150	5.99	<10	1.55	1207	8	<0.01	5	1550	86	<5	<20	30	<0.01	<10	96	<10	<1	160
6	ERK96-275	60	1.6	2.44	20	115	<5	3.09	5	26	21	153	5.28	<10	1.76	1129	6	<0.01	5	1390	112	<5	<20	56	<0.01	<10	98	<10	<1	216
7	ERK96-276	475	0.6	3.90	<5	195	<5	3.28	<1	44	22	211	8.37	<10	2.56	1068	6	0.01	8	1820	20	<5	<20	65	0.02	<10	121	<10	<1	44
8	ERK96-277	35	<0.2	3.20	<5	1160	<5	5.49	<1	25	18	112	6.05	<10	2.30	1415	4	0.02	9	1760	14	<5	<20	149	0.02	<10	102	<10	<1	68
9	ERK96-278	90	2.4	2.96	<5	510	<5	3.63	<1	16	29	1083	5.49	<10	1.90	1259	3	0.01	9	1460	26	<5	<20	80	<0.01	<10	89	<10	<1	127
10	ERK96-279	335	1.0	3.18	60	145	10	3.82	1	16	20	51	6.17	<10	2.83	1369	13	0.02	2	1090	32	<5	<20	52	<0.01	<10	116	<10	<1	83
11	ERK96-280	800	1.0	2.41	95	140	10	6.63	<1	24	12	27	5.73	<10	1.81	1631	9	<0.01	4	920	18	<5	<20	97	<0.01	<10	90	<10	<1	32
12	ERK96-281	165	0.4	2.33	30	155	10	3.74	<1	13	17	43	4.52	<10	1.80	1195	3	0.01	3	1040	20	<5	<20	62	<0.01	<10	98	<10	<1	65
13	ERK96-282	70	1.2	2.87	35	90	<5	1.26	<1	24	23	110	6.76	<10	2.35	840	6	<0.01	7	1200	42	<5	<20	24	<0.01	<10	138	<10	<1	85
14	ERK96-283	320	2.0	3.87	15	175	10	1.76	<1	17	33	72	9.29	<10	2.33	1618	7	<0.01	8	1400	176	<5	40	36	0.01	<10	171	<10	<1	236
15	ERK96-284	95	0.4	3.41	50	155	5	4.08	<1	24	20	67	7.70	<10	2.06	1955	6	<0.01	6	1380	48	<5	<20	38	<0.01	<10	127	<10	<1	128
16	ERK96-285	60	<0.2	3.06	15	180	10	4.79	<1	13	32	16	6.26	<10	2.03	1320	5	0.01	7	1370	22	<5	<20	66	<0.01	<10	135	<10	<1	70
17	ERK96-286	130	<0.2	3.29	25	185	10	4.56	<1	12	28	16	6.44	<10	2.14	1366	5	0.02	7	1510	24	<5	<20	70	0.01	<10	152	<10	<1	89
18	ERK96-287	990	1.0	3.42	<5	115	10	1.39	15	17	12	66	8.68	<10	1.42	2492	8	<0.01	3	1350	746	<5	40	18	0.01	<10	103	<10	<1	795
19	ERK96-288	160	<0.2	2.97	15	125	5	3.68	1	25	27	31	6.89	<10	1.64	1653	7	<0.01	6	1310	42	<5	<20	51	<0.01	<10	144	<10	<1	110
20	ERK96-289	295	0.2	2.24	15	95	<5	3.37	<1	31	12	61	5.08	<10	1.38	1043	4	<0.01	6	1100	36	<5	<20	47	<0.01	<10	105	<10	<1	65


Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
21	ERK96-290	95	0.8	2.00	25	115	<5	4.49	<1	72	14	90	5.93	<10	1.00	909	5	<0.01	8	1260	52	<5	20	76	<0.01	<10	92	<10	<1	53
22	ERK96-291	90	<0.2	2.45	<5	115	15	5.01	<1	31	11	15	6.17	<10	1.33	1144	5	0.02	3	1220	16	<5	<20	80	0.01	<10	87	<10	<1	73
23	ERK96-292	645	<0.2	2.60	<5	155	10	4.33	<1	20	11	11	5.36	<10	1.65	1191	4	0.02	3	1360	16	<5	<20	66	<0.01	<10	95	<10	<1	68
24	ERK96-293	>1000	0.4	3.03	10	170	10	3.00	<1	17	12	2	6.57	<10	2.06	1118	4	0.02	3	1250	24	<5	<20	62	0.01	<10	108	<10	<1	70
25	ERK96-294	115	<0.2	2.69	15	105	5	2.20	<1	15	10	3	6.11	<10	2.05	921	4	0.01	2	1300	18	<5	<20	47	<0.01	<10	86	<10	<1	69
26	ERK96-295	690	0.4	3.36	<5	130	15	1.67	<1	35	13	3	7.89	<10	2.02	1443	6	<0.01	3	1210	26	<5	<20	25	0.01	<10	91	<10	<1	77
27	ERK96-296	130	1.2	3.48	110	115	<5	4.79	<1	35	18	107	7.96	<10	2.47	1202	8	<0.01	9	1030	32	<5	<20	76	0.01	<10	136	<10	<1	-80
28	ERK96-297	10	<0.2	3.30	35	120	10	4.49	<1	11	27	48	6.70	<10	2.29	1222	5	<0.01	6	1410	22	<5	<20	82	<0.01	<10	136	<10	<1	65
29	ERK96-298	5	0.4	2.88	10	155	<5	3.51	<1	13	19	90	5.98	<10	1.71	906	4	<0.01	6	1330	20	<5	<20	56	0.01	<10	94	<10	<1	59
30	ERK96-299	10	<0.2	3.14	10	145	<5	3.41	<1	24	22	75	6.48	<10	2.19	936	5	<0.01	7	1350	18	<5	<20	64	0.01	<10	117	<10	<1	58
31	ERK96-300	5	<0.2	2.75	15	145	<5	4.51	<1	15	14	60	5.66	<10	1.89	949	4	0.01	3	1160	14	<5	<20	119	<0.01	<10	88	<10	<1	52
32	ERK96-301	10	0.6	2.89	20	115	<5	3.48	<1	15	15	82	6.17	<10	2.21	1113	4	<0.01	2	1190	18	<5	<20	86	<0.01	<10	101	<10	<1	54
33	ERK96-302	105	3.0	3.32	40	125	<5	2.98	<1	33	15	264	7.48	<10	2.30	1170	6	<0.01	4	1130	24	<5	<20	90	<0.01	<10	127	<10	<1	69
34	ERK96-303	5	1.0	2.93	20	180	<5	3.90	<1	22	19	72	5.80	<10	1.76	1062	7	<0.01	5	1260	24	<5	<20	124	0.01	<10	100	<10	<1	69
35	ERK96-304	10	1.4	3.35	10	175	<5	2.71	<1	16	18	125	6.68	<10	2.29	1032	6	<0.01	4	1220	20	<5	<20	76	<0.01	<10	106	<10	<1	74
36	ERK96-305	50	1.2	2.40	60	60	<5	3.83	<1	42	10	95	6.69	<10	1.61	1014	8	<0.01	5	1080	16	<5	<20	100	<0.01	<10	59	<10	<1	65
37	ERK96-306	10	1.0	2.85	35	130	5	4.90	<1	21	11	66	7.00	<10	1.60	1159	6	<0.01	4	1190	20	<5	20	142	<0.01	<10	72	<10	<1	73
38	ERK96-307	15	2.2	2.83	45	170	<5	3.70	<1	25	12	171	6.01	<10	1.81	1117	7	<0.01	6	1220	26	<5	<20	91	<0.01	<10	80	<10	<1	78
39	ERK96-308	10	2.4	2.71	35	130	<5	4.31	<1	21	10	150	5.98	<10	1.92	1030	5	<0.01	5	1170	26	<5	<20	123	<0.01	<10	79	<10	<1	83
40	ERK96-309	30	4.6	2.84	55	165	<5	4.47	<1	31	11	298	6.05	<10	1.86	1033	6	<0.01	6	1170	32	<5	<20	121	<0.01	<10	82	<10	<1	77
41	ERK96-310	250	<0.2	3.62	<5	225	15	2.30	<1	19	23	4	6.60	<10	3.16	1052	4	0.02	8	1380	22	<5	<20	49	<0.01	<10	112	<10	<1	87
42	ERK96-311	775	4.4	3.46	50	90	<5	2.53	<1	51	10	980	9.10	<10	2.57	1664	12	<0.01	4	1160	68	<5	<20	83	<0.01	<10	90	<10	<1	129
43	ERK96-312	10	0.4	3.09	25	215	10	4.25	<1	17	20	40	5.84	<10	2.11	1185	5	0.01	5	1240	26	<5	<20	95	<0.01	<10	104	<10	<1	84
44	ERK96-313	20	1.0	2.56	95	180	<5	2.39	4	16	16	41	5.14	<10	1.69	708	11	<0.01	3	1340	60	<5	<20	56	<0.01	<10	72	<10	<1	205
45	ERK96-314	125	4.4	3.06	20	190	<5	1.99	76	16	18	290	6.05	<10	2.19	1008	139	0.01	5	1400	908	<5	<20	42	<0.01	<10	96	<10	<1	467
46	ERK96-315	95	7.0	2.67	35	260	<5	3.00	73	20	25	552	5.21	<10	1.76	1250	148	<0.01	8	1510	1160	<5	<20	75	<0.01	<10	65	<10	1	669
47	ERK96-316	>1000	5.6	2.62	115	45	<5	0.41	4	55	22	486	>10	<10	1.82	946	20	<0.01	5	1020	122	<5	20	13	<0.01	<10	92	<10	<1	148
48	ERK96-317	310	2.8	3.33	30	95	<5	0.84	1	50	16	437	8.59	<10	2.27	1158	10	<0.01	6	1520	126	<5	<20	13	<0.01	<10	151	<10	<1	168
49	96TP-92	5	<0.2	3.03	<5	155	10	1.19	<1	24	27	26	6.33	<10	2.19	1111	4	0.02	6	1500	22	<5	<20	19	<0.01	<10	115	<10	<1	76
50	96TP-93	40	<0.2	2.71	15	80	15	1.88	<1	36	22	14	6.65	<10	2.04	1345	6	<0.01	7	1360	22	<5	<20	26	<0.01	<10	110	<10	<1	60
51	96TP-94	95	0.4	2.20	40	70	15	1.23	<1	128	16	28	8.21	<10	1.74	1219	13	<0.01	6	1430	32	<5	<20	15	<0.01	<10	107	<10	<1	69
52	96TP-96	10	<0.2	3.14	<5	110	10	2.96	<1	16	11	5	6.37	<10	2.55	1358	4	0.02	6	1330	20	<5	<20	47	0.01	<10	135	<10	<1	69
53	96TP-99	130	1.4	2.83	60	45	<5	4.34	<1	26	22	135	6.96	<10	2.74	1330	5	<0.01	4	1150	42	<5	<20	76	<0.01	<10	121	<10	<1	102
54	96TP-100	305	1.4	1.33	95	100	<5	4.83	<1	35	30	78	3.91	<10	1.03	1358	5	<0.01	6	980	22	<5	<20	79	<0.01	<10	45	<10	<1	37
55	96TP-101	65	0.2	2.28	25	170	<5	7.45	<1	17	15	16	4.49	<10	1.90	1656	3	<0.01	4	1020	14	<5	<20	140	<0.01	<10	79	<10	3	50

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
56	96TP-102	465	2.4	2.97	130	235	15	0.62	<1	64	24	141	>10	<10	2.20	1174	26	<0.01	6	1280	44	<5	20	9	<0.01	<10	104	<10	<1	80
57	96TP-103	70	<0.2	2.30	20	80	10	5.00	<1	20	33	24	4.94	<10	1.93	1289	4	<0.01	3	920	14	<5	<20	155	<0.01	<10	75	<10	<1	62
58	96TP-104	70	0.6	2.29	15	125	<5	6.23	<1	22	28	39	5.02	<10	1.80	1389	4	<0.01	5	1120	24	<5	<20	240	<0.01	<10	87	<10	<1	61
59	96TP-107	55	1.0	2.34	65	85	<5	2.75	<1	54	28	198	7.14	<10	2.21	569	7	0.01	9	1590	22	<5	<20	94	<0.01	<10	119	<10	<1	38
60	96TP-108	45	<0.2	1.98	30	60	10	1.43	<1	89	28	18	6.80	<10	2.04	473	8	0.01	7	1490	28	<5	<20	43	<0.01	<10	134	<10	<1	30

QC/DATA:

Resplit:																															
1	ERK96-270	5	7.8	3.32	165	95	70	1.80	2	25	20	95	>10	<10	1.99	1842	14	<0.01	5	1120	170	<5	20	24	<0.01	<10	117	<10	<1	275	
36	ERK96-305	70	1.0	2.35	50	55	<5	4.17	<1	39	12	93	6.48	<10	1.58	1070	8	<0.01	3	1110	20	<5	20	108	<0.01	<10	58	<10	<1	67	
Repeat:																															
1	ERK96-270	10	8.2	3.43	180	90	75	1.79	2	26	22	96	>10	<10	2.06	1862	13	<0.01	5	1100	156	<5	20	24	<0.01	<10	121	<10	<1	282	
10	ERK96-279	295	1.2	3.23	65	160	5	3.85	<1	16	21	50	6.18	<10	2.81	1374	13	0.02	3	1110	32	<5	<20	53	0.01	<10	117	<10	<1	84	
19	ERK96-288	125	0.4	3.02	20	130	10	3.70	<1	25	28	31	6.92	<10	1.66	1663	7	<0.01	6	1310	46	<5	<20	50	0.01	<10	146	<10	<1	111	
36	ERK96-305	50	1.0	2.49	70	60	<5	3.99	<1	48	10	98	7.12	<10	1.69	1051	8	<0.01	4	1160	20	<5	20	104	<0.01	<10	61	<10	<1	68	
45	ERK96-314	115	4.6	3.22	20	190	<5	2.10	78	16	19	303	6.33	<10	2.29	1053	144	0.01	6	1440	934	<5	<20	46	<0.01	<10	101	<10	<1	479	
54	96TP-100	315	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Standard:																															
GEO'96		145	1.0	1.80	70	160	5	1.90	<1	18	66	78	3.83	<10	0.98	659	<1	0.01	22	710	24	<5	<20	60	0.10	<10	72	<10	3	70	
GEO'96		145	1.0	1.78	65	165	<5	1.89	<1	18	59	80	3.91	<10	0.96	677	<1	0.01	22	730	22	<5	<20	64	0.10	<10	73	<10	3	72	

df/5401
 XLS/96Teuton#11
 Fax to Dino Vancouver 604-682-3992


 ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer



ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (250) 573-5700
Fax (250) 573-4557

CERTIFICATE OF ASSAY AS 96-5411

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

11-Oct-96

ATTENTION: DINO CREMONESE

No. of samples received: 16

Sample Type: Rock

PROJECT #: Clone

SHIPMENT #: S96-69

Samples submitted by: Ted Peters

ET #.	Tag #	Ag (g/t)	Ag (oz/t)	Co (%)	Cu (%)
2	AR-96-21	-	-	-	2.30
9	AR-96-28	45.60	1.33	-	3.31
11	SC-18-01	-	-	0.033	-
12	SC-18-02	-	-	0.047	-
14	SC-19-02	-	-	0.048	-

XLS/96Teuton

Fax to Dino Vancouver 604-682-3992


ECO-TECH LABORATORIES LTD.

per Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5411

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 16

Sample Type: Rock

PROJECT #: Clone

SHIPMENT #: S96-69

Samples submitted by: Ted Peters

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	AR-96-20	5	<0.2	2.85	<5	40	<5	7.24	<1	22	51	63	5.37	<10	2.68	1305	2	<0.01	16	1420	4	<5	<20	116	0.06	<10	148	<10	5	35
2	AR-96-21	>1000	28.0	0.27	5	40	<5	8.15	1	12	51	>10000	3.67	<10	0.08	1461	8	<0.01	8	<10	<2	<5	<20	65	0.01	<10	8	<10	7	27
3	AR-96-22	5	0.2	0.70	<5	110	<5	2.15	<1	5	27	21	1.61	<10	0.29	527	3	<0.01	1	440	4	<5	<20	37	<0.01	<10	6	<10	2	2
4	AR-96-23	30	1.0	1.53	55	45	<5	5.41	<1	13	23	51	4.78	<10	1.12	1178	8	<0.01	20	820	10	<5	<20	95	<0.01	<10	28	<10	<1	5
5	AR-96-24	60	0.4	1.22	40	65	<5	5.80	<1	16	34	30	3.19	<10	0.85	1238	31	<0.01	33	790	4	<5	<20	76	<0.01	<10	77	<10	3	3
6	AR-96-25	275	1.0	1.61	110	30	20	1.65	<1	58	18	44	9.62	<10	1.03	542	9	<0.01	41	1530	12	<5	<20	20	<0.01	<10	26	<10	<1	7
7	AR-96-26	130	2.2	0.13	80	40	<5	0.10	<1	2	116	14	1.22	<10	0.02	79	4	<0.01	4	200	238	<5	<20	4	<0.01	<10	7	<10	<1	67
8	AR-96-27	280	1.6	0.15	270	40	<5	0.06	<1	3	102	28	2.58	<10	0.01	90	7	<0.01	6	530	74	<5	<20	5	<0.01	<10	8	<10	<1	92
9	AR-96-28	>1000	>30	0.44	10	40	<5	3.18	<1	8	69	>10000	4.75	<10	0.15	1074	12	<0.01	4	10000	<2	<5	<20	25	<0.01	<10	12	10	<1	11
10	AR-96-29	150	1.8	1.31	5	45	<5	3.16	<1	26	29	876	8.28	<10	0.96	633	11	<0.01	16	1090	12	<5	<20	56	<0.01	<10	37	<10	<1	9
11	SC-18-01	>1000	0.4	2.73	65	50	<5	4.06	<1	291	122	426	8.79	<10	3.04	1412	4	<0.01	19	1410	6	<5	<20	49	0.17	<10	192	<10	<1	63
12	SC-18-02	>1000	<0.2	2.87	20	45	<5	2.43	<1	398	26	271	7.24	<10	2.77	1373	2	<0.01	17	1890	8	<5	<20	29	0.14	<10	119	<10	2	115
13	SC-19-01	935	<0.2	3.09	25	55	15	3.87	<1	150	64	49	7.72	<10	3.73	1285	1	<0.01	16	1620	8	<5	<20	45	0.16	<10	199	<10	<1	67
14	SC-19-02	>1000	<0.2	2.94	100	65	<5	3.04	<1	425	35	744	>10	<10	3.03	1448	4	<0.01	9	1350	12	<5	<20	43	0.14	<10	256	<10	<1	118
15	SC-20-01	55	<0.2	3.68	10	45	<5	3.32	<1	33	6	249	9.25	<10	2.82	1492	8	0.01	8	1670	14	<5	<20	50	0.15	<10	176	<10	<1	68
16	SC-20-02	>1000	7.2	1.67	35	70	15	1.23	<1	25	<1	141	>10	<10	1.11	718	75	<0.01	5	1190	112	<5	20	24	0.09	10	132	<10	<1	125

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
-------	-------	---------	----	------	----	----	----	------	----	----	----	----	------	----	------	----	----	------	----	---	----	----	----	----	------	---	---	---	---	----

QC/DATA:

Resplit:

1	AR-96-20	5	<0.2	3.00	<5	45	<5	6.65	<1	24	59	62	5.75	<10	2.86	1295	3	<0.01	18	1540	6	<5	<20	107	0.06	<10	159	<10	4	39
---	----------	---	------	------	----	----	----	------	----	----	----	----	------	-----	------	------	---	-------	----	------	---	----	-----	-----	------	-----	-----	-----	---	----


Repeat:

1	AR-96-20	7	<0.2	2.80	<5	40	<5	7.15	<1	22	51	67	5.31	<10	2.63	1289	3	<0.01	17	1400	4	<5	<20	115	0.05	<10	146	<10	4	36
10	AR-96-29	140	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

Standard:

GEO'96		155	1.0	1.76	65	160	<5	1.75	<1	20	61	78	3.98	<10	0.94	687	<1	0.02	22	680	18	<5	<20	54	0.12	<10	78	<10	5	72
--------	--	-----	-----	------	----	-----	----	------	----	----	----	----	------	-----	------	-----	----	------	----	-----	----	----	-----	----	------	-----	----	-----	---	----

dl/5409
 XLS/96Teuton
 Fax to Dino Vancouver 604-682-3992


 ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

ECO-TECH LABORATORIES LTD.
 10041 East Trans Canada Highway
 KAMLOOPS, B.C.
 V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AS-5431

TEUTON RESOURCES CORPORATION
 509-675 W. HASTINGS STREET
 VANCOUVER, B.C.
 V6C 1N2

Phone: 604-573-5700
 Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 4
 Sample Type: ROCK
 PROJECT #: CLONE
 SHIPMENT #: S96-62
 Samples submitted by: T. PETERS

Values in ppm unless otherwise reported

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	SC96-21-001	40	<0.2	1.77	50	55	<5	4.89	<1	54	26	82	4.09	<10	1.60	1006	<1	0.04	5	1120	10	<5	<20	92	0.12	<10	104	<10	9	43
2	SC96-21-002	10	<0.2	3.75	20	145	<5	3.79	<1	47	37	94	7.82	<10	4.09	1946	<1	0.03	15	1350	10	<5	<20	59	0.28	<10	230	<10	9	112
3	SC96-21-003	60	<0.2	3.44	90	95	<5	4.10	<1	41	34	104	8.61	<10	3.51	1792	<1	0.02	14	1350	16	<5	<20	70	0.25	<10	219	<10	2	100
4	SC96-22-001	260	0.6	1.73	170	80	<5	0.44	<1	84	22	107	5.78	<10	1.34	658	3	0.01	3	940	52	<5	<20	10	0.09	<10	56	<10	<1	94

QC/DATA:

Resplit:																														
1	SC96-21-001	50	<0.2	1.81	50	50	<5	5.35	<1	56	26	78	4.24	<10	1.68	1074	<1	0.03	5	1170	10	<5	<20	99	0.13	<10	109	<10	11	45
Repeat:																														
1	SC96-21-001	50	<0.2	1.83	50	55	<5	5.03	<1	55	27	89	4.21	<10	1.65	1032	<1	0.04	5	1160	10	<5	<20	93	0.14	<10	108	<10	11	45
Standard:																														
GEO'96		150	1.0	1.81	65	170	<5	1.78	<1	19	62	72	3.97	<10	1.07	865	<1	0.02	22	620	20	5	<20	59	0.14	<10	79	<10	9	74

d1/5433
 XLS/96Teuton
 Fax to Dino Vancouver 604-682-3992

per *Bob Muner*
 ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

0003
 ECO-TECH KAM.
 250 573 4557
 03-25-97 15:54