

DEC 23 1997

International Skyline Gold Corporation

Gold Commissioner's Office  
VANCOUVER

Bronson Highwall Claims Geochemical Assessment Report  
Liard Mining Division

NTS 104 B 11 E Latitude - 56°40'00" N Longitude - 131° 05'00" W

Work Performed  
July 24, 1997 - July 31, 1997

GEOLOGICAL SURVEY BRANCH  
BRITISH COLUMBIA

November, 1997

M. J. Moore

25,295

## Table of Contents

<b>1.0 Introduction.....</b>	<b>3</b>
<b>2.0 Geologic Setting of the Bronson Highwall Property.....</b>	<b>3</b>
<b>3.0 Exploration Program.....</b>	<b>6</b>
<b>4.0 Results of Program.....</b>	<b>6</b>
<b>5.0 Conclusions.....</b>	<b>7</b>

### Figures

<b>Figure 1: International Skyline Gold Corporation.....</b>	<b>4</b>
<b>Bronson Highwall Property Location</b>	
<b>Figure 2: Claim Map.....</b>	<b>5</b>
<b>Figure 3: Drill Hole Plan.....</b>	<b>8</b>

### Appendices

<b>Appendix 1</b>	<b>Statement of Qualifications</b>
<b>Appendix 2</b>	<b>Cost Statement</b>
<b>Appendix 3</b>	<b>Drill Logs</b>
<b>Appendix 4</b>	<b>Assays</b>

# **International Skyline Gold Corporation**

## **1.0 Introduction**

Between July 24, 1997 and July 31, 1997 International Skyline Gold Corporation performed geotechnical exploration work on its newly staked High 1 and High 2 claims. Cumulative expenditures of \$26,152.00 have been applied to update the mineral tenure of the High 1 (357915), High 2 (357916), High 3 (357917), Katy 1 (357913) and Katy 2 (357914) claims.

The Bronson Highwall claims are located within the Liard Mining District 270 km northwest of Smithers, B.C. and 80 km east of Wrangell, Alaska. Access is by aircraft to the Bronson or Johnny Mountain airstrips (see Figures 1, 2).


Claims High 1, High 2 and High 3 are owned by International Skyline Gold Corporation subject to yearly payments and a 3 % NSR of Prime Resources Group Inc. High 1 was staked on July 22, 1997. High 2 and High 3 were staked on July 23, 1997. Claims Katy 1 and Katy 2 are owned 100 % by International Skyline Gold Corporation. Both Katy 1 and Katy 2 were staked July 22, 1997. Work credit documented in this report has been issued to the Bronson Highwall claims which have new expiry dates of July 22-23, 2002.

Prior to the staking of the Bronson Highwall claims the mineral tenure belonged to Prime Resources Group Inc. Prior to 1996 the tenure was owned by Cominco Ltd and Prime Resources Group Inc. International Skyline Gold Corporation's 1997 exploration of the Bronson Highwall claims includes the surveying of seven historic drill holes, relogging of the drill holes, core splitting and geochemical analysis of unsampled porphyry mineralization.

## **2.0 Geologic Setting of the Bronson Highwall Property**

The Iskut River region is within the Intermontane Belt on the western margin of the Stikine terrane. The Bronson Highwall claims are underlain by Upper Triassic Stuhini group feldspathic greywackes and siltstones intruded by the Lower Jurassic Red Bluff K-feldspar Megacrystic porphyry. The Red Bluff intrusion is approximately 2.0 km long and 0.3 km wide trending southeast along the south side of the Bronson Creek valley. The nearby similarly trending Twin shear vein gold deposit is likely related to the gold rich Red Bluff stock.

The Red Bluff intrusion is moderately to intensely quartz, magnetite altered. Porphyry copper and gold alteration is concentrated on the south flank of the intrusion associated with quartz, magnetite alteration in the intrusion and quartz, magnetite, K-feldspar, biotite alteration in the greywackes and siltstones.



INTERNATIONAL SKYLINE GOLD


**Bronson Highwall Property Location**

Scale: 1: 300000 | FIGURE 1 | DWN:SM | Date: 28-Aug-97

ptlinee.pf


Figure 2: Claim Map

131°05'00"W



131°05'00"W

METRES



November 5, 1997  
NTS 104 B 11 E

### 3.0 Exploration Program July 24 - July 31, 1997

Personnel involved in the July exploration program were Michael Moore, Allan Chapman, Ron Chapman, Lou Straith and Karen Groth. Skyline personnel stayed in a camp near the Bronson airstrip rented from Pamicon Ltd.

The program consisted of reassessing drill holes 6, 101, 125, 126, 127, 129 and 130 of Cominco Ltd and Prime Resources Group from a porphyry perspective. In 1986 and 1994 these holes were examined and only partially split with a view towards narrow high grade gold veins and shears. In late July of 1997 the drill hole collars were surveyed by Skyline personnel. Furthermore, the drill core was relogged, fully split and assayed for gold. Knowing the gold values in the highwall of the Bronson Slope deposit are critical to fully assessing the deposit's mining feasibility.

Hole No.	East (m)	North (m)	Elev. (m)	Azim.	Dip	Length (m)	Date Start	Date Finish
6	24964	11663	775	005°	-45°	107.6	04au86	04au86
101	24943	11501	812	005°	-45°	317.4	n/a	n/a
125	24919	11555	799	005°	-45°	404.0	10jl94	14jl94
126	24919	11554	799	005°	-75°	425.3	15jl94	18jl94
127	25194	11570	805	005°	-67°	461.9	19jl94	24jl94
129	25502	11550	804	005°	-60°	382.6	26jl94	30jl94
130	25502	11551	804	005°	-45°	233.2	30jl94	01au94

### 4.0 Results of Program

Summary drill logs and 1997 assay values are located in Appendix 3 and 4, respectively.

Drill hole S-6 was logged, entirely split and assayed in 1986. Seven samples of drill core were resplit and analyzed for gold in 1997. The 1997 analysis confirmed the 1.0 g/t gold values from 76.8m-86.8m. This section of pyritic silicified siltstone is part of a gold enriched phyllic alteration adjacent to the Red Bluff porphyry stock.

Drill hole S-101 was also logged, entirely split and assayed in 1994. Three samples of drill core were resplit and analyzed for gold in 1997. The 1997 analysis confirmed the elevated gold values from 209.0m-218.0m.

Drill hole S-125 was logged and partially split in 1994. 1997 analysis of unsplit core was aimed at bracketing previous vein intersections. No significant elevation in gold values were found in the footwall or hanging wall of the historic intersections. Relogging of the holes resulted in a substantial change in the interpretation of the geology. Sections previously described as tuff were reinterpreted to be porphyry intrusive dykes. These

dykes could be interfering with the continuity of the extension of the nearby Twin gold deposit which were targeted by these holes.

Drill hole S-126 was logged and partially split in 1994. Re-logging of this hole also resulted in a reinterpretation of volcanic tuffs as porphyry intrusives. Again significant gold intersections were not bracketed in 1994. 1997 splitting and assaying of unbracketed stringers yielded a significant discovery. The biotite altered footwall of a quartz, calcite, galena stringer zone from 340.2-342.2 grades 15.7 grams gold per tonne.

Drill hole S-127 was logged and partially split in 1994. The hole contains moderately to strongly altered sedimentary rocks. Alteration is phyllic with traces to 5% pyrite disseminations. The entire hole was split and analyzed in 1997 since weak to strong pyritic mineralization was pervasive. 1997 sampling indicates the presence of wide low grade gold zones associated with stringer and disseminated pyritic zones. Highlights include 46.5 metres of 0.476 g/t gold from 126.6m-173.1m and a further 91.1 metres of 0.425 g/t gold from 196.2m-287.3m. These gold zones were intersected some 300m east in holes 129 and 139.


Drill hole S-129 was logged and partially split in 1994. This hole also contains moderately to strongly altered siltstones and greywackes. 1997 sampling and assaying revealed two gold zones associated with disseminated and vein pyrite. The gold zones are 27.5m of 0.62 g/t gold from 146.0m-173.5m and 70.9m of 0.54 g/t gold from 197.3m-268.2m.

Drill hole S-130 drilled off the same set up as S-129 was logged and partially split in 1994. Sampling of the entire hole in 1997 revealed two gold zones associated with the same disseminated and vein mineralization intersected in hole S-129. The gold zones are 17.0m of 0.542 g/t gold from 111.0m-128.0m and 77.5m of 0.598 g/t gold from 155.7- 233.2m.

## **5.0 Conclusions**

Reinterpretation of the geology in holes 125 and 126 whereby tuffs are actually porphyry intrusives increases the potential for finding the extension of Twin shear veins in this area. Sampling in the 1997 program revealed a high grade gold intersection (15.7 g/t Au over 2.0m) on the margin of a previously sampled stringer zone which grades 4.9 g/t gold over 1.6 metres. Although, the intersection does not exhibit shear zone characteristics, its location some 190 metres from Twin Zone underground workings make it an attractive target.

Infill sampling of holes 127, 129 and 130 revealed wide zones of gold mineralization which may be recoverable if this rock is mined in order to access higher grade copper, gold mineralization to the north.



ddplanb.pdf



Report by: Michael Moore  
Michael J. Moore, B.Sc.  
Project Geologist  
International Skyline Gold Corp.

Endorsed by: DA Yeager  
David A. Yeager, P. Geo.  
Chief Geologist  
International Skyline Gold Corp.



**Distribution:**

International Skyline Gold Corporation

Ministry of Employment and Investment  
Energy and Minerals Division - Mineral Titles Branch


**Appendix 1**  
**Statement of Qualifications**

## STATEMENT OF QUALIFICATIONS

I, David A. Yeager, do hereby state:

1. That I am the Chief Geologist of International Skyline Gold Corporation, with offices located at 910 - 925 West Georgia Street, Vancouver, B.C.
2. That I am a member of the Association of Professional Engineers and Geoscientists of the Province of British Columbia.
3. That I am a graduate of the University of British Columbia (B.Sc., 1972) and have been employed as an exploration and mining geologist since that time.
4. That my experience has given me considerable knowledge in geological, geochemical and geophysical prospecting techniques as well as in the planning, execution and evaluation of exploration drilling programs.
5. That I have visited and am familiar with the Bronson Slope property and the Bronson Slope porphyry deposit.
6. That the program described in this report was performed under my supervision.
7. That the work was performed by geologist Michael M. Moore, B.Sc., in whose work I have complete confidence.

Signed and Sealed on the 19 day of December, 1997.



DA Yeager

David A. Yeager, P. Geo.

## STATEMENT OF QUALIFICATIONS

I, Michael J. Moore, do hereby state:

1. That I am the Project Geologist of International Skyline Gold Corporation, with offices located at 910 - 925 West Georgia Street, Vancouver, B.C.
2. That I am a graduate of the University of British Columbia (B.Sc., 1987) and have been employed as an exploration and mining geologist for six of the last ten years.
3. That my experience has given me considerable knowledge in geological, geochemical and geophysical prospecting techniques as well as in the planning, execution and evaluation of exploration drilling programs.
4. That I have visited and am familiar with the Bronson Slope property and the Bronson Slope porphyry deposit.
5. That the program described in this report was performed by myself.

Signed on the 22 day of December, 1997.



Michael J. Moore, B.Sc. Geo.

**Appendix 2**  
**Cost Statement**

## International Skyline Gold Highwall Program Cost Statement

labour - 1 cook \$200/day; 1 geologist \$225/day; 1 surveyor/geotechnician \$225/day; 1 camp manager/coresplitter \$200/day 1 coresplitter \$150/day for 8 days	\$8000.00
Assay costs - 790 samples analyzed for gold Chemex lab costs \$14.85/sample	\$11732.00
Accommodations - July 24-31, 1997; 5 persons for 8 days; Pamicon camp rental (not including fuel) \$15/day/person	\$600.00
Camp costs - July 24 -31; 6 barrels fuel @ \$320/barrel (includes cost to fly in fuel); food \$800.00	\$2720.00
Airplane costs - 2 persons Vancouver to Smithers 5 persons Smithers to Bronson	\$3100.00
Report costs - 5 man days @ \$225.00/day	<u>\$1125.00</u>
	<b>\$27277.00</b>

**Appendix 3**  
**Drill logs**

<b>DDH CS6 ASSAY (1997) TABLE</b>								
Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm	
0 - 2.1m Overburden	2.1	3.7	n/a	1.6	0.140	0.7	187	
2.1 - 5.3m Arkose/Greywacke - very fine grained arenaceous unit	3.7	5.3	n/a	1.6	0.150	0.5	154	
5.3 - 42.0m Variably altered Arkose/ Siltstone	5.3	7.3	n/a	2.0	0.450	1.2	254	
	7.3	9.3	n/a	2.0	0.290	2.0	242	
	9.3	11.0	n/a	1.7	0.210	3.3	101	
	11.0	12.8	n/a	1.8	0.160	1.5	208	
	12.8	13.8	n/a	1.0	0.110	1.2	9	
	13.8	15.8	n/a	2.0	0.220	1.4	154	
	15.8	17.8	n/a	2.0	0.140	1.0	29	
	17.8	19.8	n/a	2.0	0.170	1.5	250	
	19.8	21.8	n/a	2.0	0.150	0.5	80	
	21.8	23.8	n/a	2.0	0.120	0.7	88	
	23.8	25.8	n/a	2.0	0.050	0.5	29	
	25.8	27.8	n/a	2.0	0.090	1.7	166	
	27.8	29.8	n/a	2.0	0.360	1.4	89	
	29.8	31.8	n/a	2.0	0.230	0.8	73	
	42.0 - 47.9m Siltstone	31.8	33.8	n/a	2.0	0.180	3.8	9
33.8		35.8	n/a	2.0	0.130	3.6	166	
35.8		37.8	n/a	2.0	0.210	1.9	43	
37.8		39.8	n/a	2.0	0.120	1.1	35	
39.8		41.8	n/a	2.0	0.220	1.1	11	
41.8		43.8	n/a	2.0	0.220	2.1	181	
43.8		45.8	n/a	2.0	0.210	1.3	100	
45.8		47.9	n/a	2.1	0.190	1.5	55	
47.9 - 49.7m quartz, chlorite, pyrite mineral zone		47.9	49.7	n/a	1.8	5.830	48.8	144
49.7 - 50.8m Fault zone		49.7	50.8	n/a	1.1	0.190	1.3	12
50.8 - 69.5m Siltstone	50.8	52.8	n/a	2.0	0.550	1.2	82	
	52.8	54.8	n/a	2.0	0.550	1.2	281	
	54.8	56.8	n/a	2.0	0.290	0.6	251	
	56.8	58.8	n/a	2.0	0.190	1.0	288	
	58.8	60.8	n/a	2.0	1.030	1.9	51	
	60.8	62.8	n/a	2.0	0.820	7.8	180	
	62.8	64.8	n/a	2.0	0.120	0.4	21	
	64.8	66.8	n/a	2.0	0.310	0.0	10	
69.5 - 72.8m Arkose-Greywacke	66.8	68.8	n/a	2.0	0.420	0.8	203	
	68.8	70.8	n/a	2.0	1.710	0.7	140	
72.8 - 89.9m Silicified Siltstone - 10% pyrite	70.8	72.8	n/a	2.0	0.550	1.5	151	
	72.8	74.8	n/a	2.0	0.190	0.7	211	



Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	74.8	76.8	5349	2.0	0.315	0.8	336
	76.8	78.8	5350	2.0	1.075	4.4	400
	78.8	80.8	5351	2.0	0.610	4.3	457
	80.8	82.8	5352	2.0	1.270	2.6	495
	82.8	84.8	5354	2.0	1.215	1.7	328
	84.8	86.8	5355	2.0	3.680	2.1	516
	86.8	88.8	5356	2.0	0.360	1.2	260
89.9 - 107.6m Arkose-Greywacke	88.8	90.8	n/a	2.0	0.060	0.6	118
	90.8	92.8	n/a	2.0	0.370	0.6	129
	92.8	94.8	n/a	2.0	0.170	0.0	88
	94.8	96.8	n/a	2.0	0.180	0.6	233
	96.8	98.8	n/a	2.0	0.270	0.0	65
	98.8	100.8	n/a	2.0	0.240	0.6	81
	100.8	102.8	n/a	2.0	0.190	0.0	111
	102.8	104.8	n/a	2.0	0.240	1.3	40
107.6m End of Hole	104.8	107.6	n/a	2.8	0.250	0.8	114

DDH C101 ASSAY (1997) TABLE							
Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
0 - 123.8m Feldspathic Wacke/Siltstone	3.0	6.0	n/a	3.0	0.000	0.0	13
	6.0	9.0	n/a	3.0	0.000	0.9	259
	9.0	12.0	n/a	3.0	0.000	0.5	134
	12.0	15.0	n/a	3.0	0.000	0.0	7
	15.0	18.0	n/a	3.0	0.000	0.0	11
	18.0	21.0	n/a	3.0	0.000	0.0	5
	21.0	24.0	n/a	3.0	0.000	0.0	6
	24.0	27.0	n/a	3.0	0.000	0.0	10
	27.0	30.0	n/a	3.0	0.000	0.0	15
	30.0	33.0	n/a	3.0	0.000	0.0	157
	33.0	36.0	n/a	3.0	0.000	0.0	44
	36.0	39.0	n/a	3.0	0.000	0.0	4
	39.0	42.0	n/a	3.0	0.000	0.0	25
	42.0	45.0	n/a	3.0	0.000	0.0	37
	45.0	48.0	n/a	3.0	0.000	0.0	81
	48.0	51.0	n/a	3.0	0.000	0.0	88
	51.0	54.0	n/a	3.0	0.040	0.0	165
	54.0	55.3	n/a	1.3	0.040	0.0	179
	55.3	57.0	n/a	1.7	0.032	0.0	165
	57.0	60.0	n/a	3.0	0.000	0.0	67
	60.0	63.0	n/a	3.0	0.132	1.0	135
	63.0	66.0	n/a	3.0	0.184	0.0	154
	66.0	69.0	n/a	3.0	0.044	0.4	149
	69.0	72.0	n/a	3.0	0.040	0.0	136
	72.0	75.0	n/a	3.0	0.032	0.4	92
	75.0	78.0	n/a	3.0	0.028	0.0	68
	78.0	81.0	n/a	3.0	0.032	0.0	84
	81.0	83.0	n/a	2.0	0.024	0.0	115
	83.0	86.0	n/a	3.0	0.026	0.0	137
	86.0	89.0	n/a	3.0	0.024	0.0	41
	89.0	92.0	n/a	3.0	0.000	1.6	72
	92.0	95.0	n/a	3.0	0.000	0.6	27
	95.0	98.0	n/a	3.0	0.000	0.5	24
	98.0	101.0	n/a	3.0	0.000	0.7	50
	101.0	102.1	n/a	1.1	0.000	1.0	54
	102.1	104.0	n/a	1.9	0.000	0.8	116
	104.0	107.0	n/a	3.0	0.000	0.8	65
	107.0	110.0	n/a	3.0	0.000	0.9	74

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	110.3	113.0	n/a	2.7	0.000	0.0	47
	113.0	116.0	n/a	3.0	0.000	0.0	34
	116.0	119.0	n/a	3.0	0.000	0.5	50
	119.0	122.0	n/a	3.0	0.000	1.4	104
	122.0	123.8	n/a	1.8	0.000	0.9	116
123.8 - 220.7m Feldspathic Wacke	123.8	125.0	n/a	1.2	0.024	1.0	108
	125.0	128.0	n/a	3.0	0.020	1.0	142
	128.0	131.0	n/a	3.0	0.000	1.4	165
	131.0	134.0	n/a	3.0	0.024	1.4	135
	134.0	137.0	n/a	3.0	0.020	1.8	195
	137.0	140.0	n/a	3.0	0.022	1.6	167
	140.0	143.0	n/a	3.0	0.028	2.4	238
	143.0	146.0	n/a	3.0	0.020	1.7	163
	146.0	149.0	n/a	3.0	0.032	1.2	126
	149.0	152.0	n/a	3.0	0.020	1.0	117
	152.0	155.0	n/a	3.0	0.000	0.7	90
	155.0	158.0	n/a	3.0	0.028	0.7	188
	158.0	161.0	n/a	3.0	0.000	0.0	147
	161.0	164.0	n/a	3.0	0.020	0.8	120
	164.0	167.0	n/a	3.0	0.032	0.7	111
	167.0	170.0	n/a	3.0	0.022	1.3	160
	170.0	173.0	n/a	3.0	0.024	1.2	136
	173.0	176.0	n/a	3.0	0.044	2.0	124
	176.0	179.0	n/a	3.0	0.036	1.0	120
	179.0	182.0	n/a	3.0	0.026	1.5	157
	182.0	185.0	n/a	3.0	0.042	1.4	157
	185.0	188.0	n/a	3.0	0.042	1.3	190
	188.0	191.0	n/a	3.0	0.040	1.0	141
	191.0	194.0	n/a	3.0	0.052	1.4	289
	194.0	197.0	n/a	3.0	0.082	1.0	166
	197.0	200.0	n/a	3.0	0.092	1.4	265
	200.0	203.0	n/a	3.0	0.180	2.5	517
	203.0	206.0	n/a	3.0	0.140	2.3	241
	206.0	207.5	n/a	1.5	0.116	1.6	211
	207.5	209.0	n/a	1.5	0.070	1.8	394
	209.0	212.0	5357	3.0	0.285	4.7	257
	212.0	215.0	5358	3.0	0.355	4.2	169
	215.0	218.0	5359	3.0	0.360	5.1	431
220.7 - 240.8m Biotite altered Feldspathic Wacke/Siltstone	218.0	221.0	n/a	3.0	0.100	1.6	135

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	221.0	224.0	n/a	3.0	0.136	0.9	124
	224.0	227.0	n/a	3.0	0.112	1.0	195
	227.0	230.0	n/a	3.0	0.100	1.3	206
	230.0	233.0	n/a	3.0	0.280	2.0	212
	233.0	236.0	n/a	3.0	0.260	2.8	211
	236.0	239.0	n/a	3.0	0.382	3.5	189
240.8 - 314.8m K-feldspar Porphyry	239.0	242.0	n/a	3.0	0.020	1.8	142
	242.0	245.0	n/a	3.0	0.000	0.0	14
	245.0	248.0	n/a	3.0	0.000	0.4	18
	248.0	251.0	n/a	3.0	0.040	0.0	25
	251.0	254.0	n/a	3.0	0.000	0.4	8
	254.0	257.0	n/a	3.0	0.000	0.0	34
	257.0	260.0	n/a	3.0	0.000	0.4	61
	260.0	263.0	n/a	3.0	0.000	0.0	25
	263.0	266.0	n/a	3.0	0.000	0.0	11
	266.0	269.0	n/a	3.0	0.000	0.0	17
	269.0	272.0	n/a	3.0	0.000	0.0	26
	272.0	275.0	n/a	3.0	0.000	0.0	11
	275.0	278.0	n/a	3.0	0.000	0.0	13
	278.0	281.0	n/a	3.0	0.000	0.4	17
	281.0	284.0	n/a	3.0	0.000	0.0	3
	284.0	287.0	n/a	3.0	0.000	0.5	13
	287.0	290.0	n/a	3.0	0.000	0.5	80
	290.0	293.0	n/a	3.0	0.000	0.0	48
	293.0	296.0	n/a	3.0	0.000	0.0	7
	296.0	299.0	n/a	3.0	0.024	0.0	19
	299.0	302.0	n/a	3.0	0.060	0.8	58
	302.0	305.0	n/a	3.0	0.020	0.0	87
	305.0	308.0	n/a	3.0	0.000	0.7	88
	308.0	311.0	n/a	3.0	0.000	0.0	16
	311.0	314.0	n/a	3.0	0.000	0.5	97
314.8m End of Hole	314.0	314.8	n/a	0.8	0.024	0.0	185

DDH C125 ASSAY (1997) TABLE							
Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
0 - 2.6m Overburden	3.5	3.8	n/a	0.3	0.874	1.4	49
2.6 - 39.4m Greywacke minor Siltstone and Volcanic Fragmental							
	11.2	11.7	n/a	0.5	0.093	0.1	44
	12.0	12.3	n/a	0.3	0.289	0.3	73
	16.3	17.2	n/a	0.9	0.104	0.1	68
	18.5	18.7	n/a	0.2	0.203	0.2	37
	20.8	21.8	n/a	1.0	0.116	0.5	77
	26.0	26.3	n/a	0.3	0.129	0.3	89
	28.3	28.6	n/a	0.3	0.216	1.3	52
	29.8	30.2	n/a	0.4	0.132	1.3	160
	35.0	35.5	n/a	0.5	0.116	0.8	128
39.4 - 49.2m Volcanic Fragmental							
	40.5	41.1	n/a	0.6	0.077	0.1	40
	41.1	42.2	n/a	1.1	0.159	0.5	90
	45.1	46.1	n/a	1.0	0.047	1.2	38
49.2 - 185.8m Greywacke							
	51.1	51.4	n/a	0.3	0.086	0.8	46
	51.4	52.2	n/a	0.8	0.103	0.8	111
	52.2	52.4	n/a	0.2	0.103	13.6	1759
	52.4	53.7	n/a	1.3	0.101	0.1	191
	58.5	59.3	n/a	0.8	0.133	1.1	148
	63.3	63.6	n/a	0.3	0.135	2.2	268
	64.8	65.2	n/a	0.4	0.100	2.0	311
	65.8	66.2	n/a	0.4	0.111	2.5	277

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	67.5	69.0	n/a	1.5	0.103	0.8	188
	70.5	71.0	n/a	0.5	0.135	1.0	233
	71.3	72.1	n/a	0.8	0.115	1.6	155
	75.3	75.8	n/a	0.5	0.104	0.1	112
	75.8	76.0	n/a	0.2	0.120	1.1	177
	79.7	80.1	n/a	0.4	0.117	2.1	125
	82.3	82.6	n/a	0.3	0.120	0.1	71
	83.1	83.4	n/a	0.3	0.069	1.4	47
	83.4	83.7	n/a	0.3	0.020	0.5	19
	83.7	84.9	n/a	1.2	0.066	0.7	42
	87.0	87.5	n/a	0.5	0.060	0.1	70
	87.9	88.5	n/a	0.6	0.035	0.1	141
	88.5	90.0	n/a	1.5	0.509	0.7	186
	90.0	91.0	n/a	1.0	0.104	0.5	214
	96.3	96.6	n/a	0.3	0.172	0.4	60
	99.2	100.0	5360	0.8	0.060		
	100.0	100.8	5361	0.8	0.080		
	100.8	101.4	n/a	0.6	0.097	0.2	74
	101.4	102.9	n/a	1.5	0.083	1.7	158
	108.0	108.9	n/a	0.9	0.059	1.5	127
	108.9	109.9	n/a	1.0	0.076	1.5	142
	114.1	114.5	n/a	0.4	0.110	1.5	278
	117.7	119.3	n/a	1.6	0.262	2.8	258
	119.3	120.5	n/a	1.2	0.077	1.9	134

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	123.9	124.2	n/a	0.3	0.176	2.3	438
	124.2	129.7	n/a	5.5	0.116	2.2	134
	129.7	135.7	n/a	6.0	0.131	4.1	82
	140.0	140.2	n/a	0.2	0.044	0.1	34
	141.0	141.3	n/a	0.3	0.020	1.5	22
	148.3	148.6	n/a	0.3	0.047	0.7	65
	148.9	149.2	n/a	0.3	0.194	2.0	355
	154.7	155.2	n/a	0.5	0.039	1.0	36
	156.1	157.4	n/a	1.3	0.025	1.2	49
	164.0	164.3	n/a	0.3	0.021	1.1	50
	164.3	165.2	n/a	0.9	0.056	0.1	19
	165.2	165.5	n/a	0.3	0.128	1.2	265
	168.6	169.1	n/a	0.5	0.057	1.4	157
	169.1	169.3	n/a	0.2	0.190	3.4	538
	170.7	171.1	n/a	0.4	0.076	0.1	30
	171.6	172.3	n/a	0.7	0.177	4.6	2059
	172.3	172.7	n/a	0.4	0.109	1.2	344
	172.7	173.2	n/a	0.5	0.213	0.1	12
	175.2	175.6	n/a	0.4	0.228	0.1	58
	175.6	175.7	n/a	0.1	0.186	2.5	691
	176.6	177.1	n/a	0.5	0.057	0.5	167
	180.8	182.2	n/a	1.4	0.121	0.2	208
	182.5	182.9	n/a	0.4	0.116	0.3	22
	182.9	183.7	n/a	0.8	0.076	1.7	54
	183.7	184.6	n/a	0.9	0.058	0.3	28
	184.6	185.4	n/a	0.8	0.179	0.1	19

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	185.4	185.7	n/a	0.3	0.084	0.9	20
185.8 - 220.4m K-feldspar Porphyry	187.3	187.8	n/a	0.5	0.055	0.2	120
	192.9	193.3	n/a	0.4	0.111	0.2	11
	194.6	196.0	n/a	1.4	0.060	1.3	18
	196.3	196.6	n/a	0.3	0.071	1.0	10
	200.2	201.7	n/a	1.5	0.086	1.3	10
	203.8	205.7	n/a	1.9	0.028	1.8	10
	207.3	208.5	n/a	1.2	0.066	1.6	10
	214.9	216.3	n/a	1.4	0.052	1.8	10
	216.3	217.1	n/a	0.8	0.098	0.6	10
	217.4	217.7	n/a	0.3	0.058	1.8	459
	217.7	218.2	n/a	0.5	0.085	1.4	110
220.4 - 229.6m Greywacke/Volcanic Fragmental	220.4	220.7	n/a	0.3	0.150	2.8	144
	220.7	222.0	n/a	1.3	0.035	2.0	419
	222.9	223.1	n/a	0.2	0.220	2.5	254
	223.1	223.7	n/a	0.6	0.216	3.5	238
	223.7	224.1	n/a	0.4	0.166	2.5	550
	225.4	226.0	n/a	0.6	0.189	3.1	10
	228.5	229.2	n/a	0.7	0.060	1.3	10
229.6 - 240.2m K-feldspar Porphyry	231.2	232.1	n/a	0.9	0.095	0.2	10
	235.8	236.9	n/a	1.1	0.091	1.5	10
	236.9	237.1	n/a	0.2	0.035	2.3	10
	237.1	238.4	n/a	1.3	0.049	1.1	10
240.2 - 244.0m Volcanic Fragmental	240.0	241.5	n/a	1.5	0.056	1.0	149



Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
244.0 - 268.6m K-feldspar Porphyry							
268.6 - 287.6m Volcanic Fragmental/Greywacke	250.3	251.9	n/a	1.6	0.072	2.0	446
	251.9	252.1	n/a	0.2	0.332	12.1	6805
	252.1	252.4	n/a	0.3	0.042	1.3	2271
	253.6	254.2	n/a	0.6	0.070	0.1	643
	254.2	254.8	n/a	0.6	0.080	1.2	981
	257.4	258.9	n/a	1.5	0.029	0.1	82
	258.9	259.1	n/a	0.2	0.028	0.9	897
	259.1	260.1	n/a	1.0	0.057	1.2	645
	264.2	265.5	n/a	1.3	0.020	0.6	107
	266.8	267.1	n/a	0.3	0.085	2.3	639
	267.1	267.5	n/a	0.4	0.047	0.4	361
	267.5	267.9	n/a	0.4	0.020	0.1	181
	267.9	268.6	n/a	0.7	0.020	2.3	395
	268.6	269.8	n/a	1.2	0.073	3.0	634
	269.8	270.6	n/a	0.8	0.511	11.2	1003
	270.6	270.8	n/a	0.2	0.409	23.3	1301
	270.8	272.2	n/a	1.4	0.021	3.4	544
	272.2	273.1	n/a	0.9	0.098	3.3	841
	273.1	273.4	n/a	0.3	0.410	4.1	655
	273.4	274.2	n/a	0.8	0.112	2.7	477
	274.2	275.0	n/a	0.8	0.094	1.6	459
	275.0	275.6	n/a	0.6	0.154	3.2	507
	275.6	276.6	n/a	1.0	0.075	0.9	248
	276.6	276.9	n/a	0.3	0.061	2.3	269
	276.9	277.2	n/a	0.3	0.048	0.1	101
	277.2	277.5	n/a	0.3	0.127	2.9	348
	277.5	279.1	n/a	1.6	0.052	1.3	230
	279.1	280.1	n/a	1.0	0.020	0.8	145
	280.1	280.4	n/a	0.3	0.166	4.1	589
	280.4	281.2	n/a	0.8	0.041	0.7	468
	281.2	281.7	n/a	0.5	0.355	1.5	791
	281.7	282.0	n/a	0.3	0.151	1.5	299
	282.0	282.2	n/a	0.2	0.126	2.1	1120
	282.2	283.3	n/a	1.1	0.020	1.2	429

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	283.3	284.4	n/a	1.1	0.072	2.9	532
	284.4	285.2	n/a	0.8	0.103	4.0	401
	285.2	286.7	n/a	1.5	0.124	5.9	739
	286.7	287.6	n/a	0.9	0.204	6.3	533
287.6 - 307.5m Greywacke/Volcanic Fragmental	287.6	287.8	n/a	0.2	0.126	3.8	572
	287.8	288.3	n/a	0.5	0.020	2.1	87
	293.6	294.6	n/a	1.0	0.084	4.1	474
	294.6	295.4	n/a	0.8	0.080	2.6	468
	296.5	297.3	n/a	0.8	0.063	3.3	273
	297.8	298.1	n/a	0.3	0.101	3.4	218
	300.8	301.1	n/a	0.3	0.058	3.1	220
	301.1	302.1	n/a	1.0	0.082	2.0	128
	302.1	302.7	n/a	0.6	0.113	3.0	249
	302.7	304.2	n/a	1.5	0.148	2.3	257
	304.2	304.6	n/a	0.4	0.154	23.1	2109
	304.6	306.5	n/a	1.9	0.155	9.8	1003
	306.5	307.4	n/a	0.9	0.187	14.2	1324
	307.4	307.5	n/a	0.1	0.311	6.2	1006
307.5 - 317.6m K-feldspar Porphyry	307.5	308.1	n/a	0.6	0.137	20.4	2605
	308.1	308.8	n/a	0.7	0.175	5.0	820
	308.8	309.7	n/a	0.9	0.263	10.5	1487
	309.7	311.2	n/a	1.5	0.107	15.0	2009
	311.2	311.9	n/a	0.7	0.059	1.6	443
	311.9	313.4	n/a	1.5	0.096	15.9	3496
	313.4	314.2	n/a	0.8	0.039	9.4	2485
	314.2	314.9	n/a	0.7	0.019	0.5	311
	314.9	315.7	n/a	0.8	0.061	4.8	862
	315.7	316.6	n/a	0.9	0.159	15.4	1014
	316.6	317.6	n/a	1.0	0.109	9.1	665
317.6 - 404.0m Greywacke	317.6	318.9	n/a	1.3	0.291	14.1	1098
	318.9	321.7	5362	2.8	0.050		
	321.7	323.2	n/a	1.5	0.166	1.3	405
	323.2	323.5	n/a	0.3	0.398	3.7	1216
	323.5	325.0	n/a	1.5	0.127	0.3	225
	325.0	325.9	5364	0.9	0.025		

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	325.9	327.4	n/a	1.5	0.221	0.5	87
	327.4	327.6	n/a	0.2	0.468	3.0	757
	327.6	328.1	n/a	0.5	0.175	2.2	319
	328.1	328.6	n/a	0.5	0.108	0.7	55
	328.6	329.4	n/a	0.8	0.945	2.3	158
	329.4	329.8	n/a	0.4	0.106	0.1	117
	329.8	330.7	n/a	0.9	0.138	0.1	269
	330.7	332.2	n/a	1.5	0.316	0.1	222
	332.2	332.8	5365	0.6	0.160		
	332.8	333.4	n/a	0.6	0.110	0.1	86
	333.4	333.8	n/a	0.4	0.082	0.1	181
	333.8	335.3	n/a	1.5	0.125	1.0	371
	335.3	336.6	5366	1.3	0.505		
	336.6	338.1	n/a	1.5	0.676	0.1	422
	338.1	338.3	n/a	0.2	1.900	6.1	510
	338.3	339.8	n/a	1.5	2.750	3.0	214
	339.8	340.3	n/a	0.5	0.162	2.6	91
	340.3	341.4	n/a	1.1	0.599	2.4	97
	341.4	341.7	n/a	0.3	0.741	1.7	242
	341.7	342.6	n/a	0.9	0.367	2.6	195
	342.6	343.3	n/a	0.7	0.187	2.5	414
	343.3	343.7	n/a	0.4	0.345	2.9	411
	343.7	343.9	n/a	0.2	2.350	4.6	424
	343.9	345.4	n/a	1.5	0.020	1.0	193
	345.4	347.0	n/a	1.6	0.584	2.2	190
	347.0	347.8	n/a	0.8	0.055	2.8	106
	347.8	348.0	n/a	0.2	4.050	5.7	855
	348.0	349.5	n/a	1.5	0.123	1.9	347
	349.5	350.1	n/a	0.6	0.217	2.2	525
	350.1	350.7	n/a	0.6	0.079	3.8	167
	350.7	352.4	n/a	1.7	0.056	1.0	123
	364.6	367.0	n/a	2.4	0.047	1.4	101
	367.0	367.2	n/a	0.2	0.020	0.1	63
	384.2	385.7	n/a	1.5	0.213	1.3	206
	385.7	386.1	n/a	0.4	0.163	0.4	236
	386.1	387.6	n/a	1.5	0.148	1.0	184

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	390.4	390.6	n/a	0.2	0.134	0.7	290
	390.6	392.1	n/a	1.5	0.117	1.1	156
	394.0	395.1	n/a	1.1	0.077	0.4	122
	395.1	396.6	n/a	1.5	0.051	1.2	100
	398.7	400.4	n/a	1.7	0.075	0.4	45
	400.4	400.7	n/a	0.3	0.061	0.1	69
	400.7	401.0	n/a	0.3	0.020	0.1	49
	401.0	401.2	n/a	0.2	0.020	0.4	115
404.0m End of Hole	401.2	402.7	n/a	1.5	0.083	1.5	157

DDH C126 ASSAY (1997) TABLE							
Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
0 - 3.0m Overburden	3.2	4.7	n/a	1.5	0.087	2.7	190
3.0 - 64.2m Greywacke minor Siltstone/Volcanic Fragmental							
	8.8	9.5	n/a	0.7	0.078	6.1	108
	12.7	13.2	n/a	0.5	0.131	3.2	72
	13.2	13.6	n/a	0.4	0.747	3.3	106
	13.6	14.1	n/a	0.5	0.088	2.6	202
	14.1	15.0	n/a	0.9	0.066	2.8	85
	15.0	16.5	n/a	1.5	0.076	1.9	210
	17.1	17.2	n/a	0.1	0.024	1.7	85
	17.2	17.7	n/a	0.5	0.020	1.8	52
	17.7	18.8	n/a	1.1	0.029	1.5	47
	18.8	19.2	n/a	0.4	0.028	2.4	53
	19.2	19.5	n/a	0.3	0.087	2.9	343
	28.2	28.5	n/a	0.3	0.446	12.4	523
	30.5	31.1	n/a	0.6	0.037	1.6	93
	32.1	32.3	n/a	0.2	0.058	2	34
	32.3	33.1	n/a	0.8	0.030	2.4	146
	34.6	35.4	n/a	0.8	0.036	3.2	161
	35.4	36.9	n/a	1.5	0.047	2.5	181
	36.9	37.9	n/a	1.0	0.059	3	96
	37.9	38.3	n/a	0.4	0.114	4.7	324
	38.3	38.9	n/a	0.6	0.037	0.1	43
	38.9	39.8	n/a	0.9	0.066	0.8	61
	39.8	40.0	n/a	0.2	0.037	0.4	114
	41.7	42.2	n/a	0.5	0.130	0.1	96
	50.5	51.4	n/a	0.9	0.043	0.3	274
	51.4	51.6	n/a	0.2	0.139	2	224
	51.6	52.0	n/a	0.4	0.332	1.2	115
	52.0	52.2	n/a	0.2	0.094	1.4	131

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	53.0	54.6	n/a	1.6	0.060	0.6	122
	54.6	54.9	n/a	0.3	0.294	2.1	178
	54.9	55.4	n/a	0.5	0.251	1.7	79
	55.4	55.5	n/a	0.1	0.057	2.8	158
	56.0	56.1	n/a	0.1	0.125	2.7	244
	61.9	62.2	n/a	0.3	0.020	0.4	188
	62.2	63.7	n/a	1.5	0.078	1.3	184
	63.7	64.2	n/a	0.5	0.073	1	77
64.2 - 78.2m Volcanic Fragmental							
	66.2	66.4	n/a	0.2	0.035	1.2	32
	68.3	68.5	n/a	0.2	0.038	2.1	142
	68.5	69.4	n/a	0.9	0.038	4.4	49
	69.4	69.5	n/a	0.1	0.143	2.5	256
	69.5	70.3	n/a	0.8	0.027	26	24
	73.9	74.1	n/a	0.2	0.061	2.5	37
	74.1	75.4	n/a	1.3	0.043	0.6	28
	75.4	75.6	n/a	0.2	0.026	0.9	21
	75.6	76.2	n/a	0.6	0.042	1.4	22
78.2 - 254.4m Greywacke minor Volcanic Fragmental/Siltstone							
	77.9	78.2	n/a	0.3	0.329	1.2	78
	82.2	83.1	n/a	0.9	0.072	1.3	80
	85.3	86.0	n/a	0.7	0.085	2	370
	88.9	89.5	n/a	0.6	0.054	1.2	161
	89.5	89.9	n/a	0.4	0.070	1.9	121
	98.3	99.9	n/a	1.6	0.084	2.3	107
	99.9	100.2	n/a	0.3	0.211	3	286
	100.2	101.7	n/a	1.5	0.094	2.8	210
	102.6	104.1	n/a	1.5	0.283	0.9	129
	104.1	104.3	n/a	0.2	0.290	1.4	234
	104.3	105.3	n/a	1.0	0.210	1.2	149

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	105.3	105.6	n/a	0.3	0.266	1.1	154
	110.3	111.0	n/a	0.7	0.215	2.3	18
	111.0	112.1	n/a	1.1	0.115	0.4	125
	112.1	113.2	n/a	1.1	0.138	0.1	101
	113.2	114.9	5367	1.7	0.070		
	114.9	116.4	n/a	1.5	8.300	1.6	150
	116.4	118.4	5368	2.0	0.060		
	118.4	120.9	5369	2.5	0.075		
	120.9	121.9	n/a	1.0	0.131	6.5	42
	121.9	122.2	n/a	0.3	0.145	0.6	52
	122.2	123.7	n/a	1.5	0.178	1	133
	123.7	125.0	n/a	1.3	0.236	0.1	51
	125.0	126.5	n/a	1.5	1.400	0.8	123
	126.5	127.5	5370	1.0	0.070		
	127.5	128.5	5371	1.0	0.080		
	138.6	138.9	n/a	0.3	0.105	0.1	137
	138.9	139.9	n/a	1.0	0.150	0.6	281
	139.9	140.0	n/a	0.1	0.327	1.5	524
	140.0	141.5	n/a	1.5	0.096	0.1	207
	141.5	142.6	n/a	1.1	0.096	0.9	170
	142.6	143.1	n/a	0.5	0.079	0.1	255
	143.1	143.5	n/a	0.4	0.125	0.1	193
	143.5	144.8	n/a	1.3	0.156	0.8	213
	144.8	146.3	n/a	1.5	0.152	0.1	202
	146.3	146.6	n/a	0.3	0.093	0.4	306
	146.6	147.1	n/a	0.5	0.109	0.1	32
	147.1	148.4	n/a	1.3	0.134	0.8	246
	148.4	149.0	n/a	0.6	0.121	1.3	438
	149.0	149.4	n/a	0.4	0.085	0.6	178
	149.4	149.7	n/a	0.3	0.097	0.1	69
	149.7	150.2	n/a	0.5	0.205	3.2	155
	150.2	151.0	n/a	0.8	0.108	1	313
	151.0	152.2	n/a	1.2	0.091	2	411
	152.2	153.0	n/a	0.8	0.190	2.5	149
	153.0	154.4	n/a	1.4	0.066	0.6	213
	154.4	155.1	n/a	0.7	0.042	1.4	204
	155.1	156.1	n/a	1.0	0.057	1.6	222

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	156.1	156.6	n/a	0.5	0.060	1.6	107
	156.6	158.1	n/a	1.5	0.061	0.4	181
	158.1	159.7	n/a	1.6	0.047	1.2	73
	159.7	160.0	n/a	0.3	0.050	1.2	137
	160.0	160.7	n/a	0.7	0.062	2.2	172
	160.7	161.8	n/a	1.1	0.032	1.4	60
	168.7	170.2	n/a	1.5	0.171	0.5	55
	170.2	170.4	n/a	0.2	0.024	1	133
	170.4	171.0	n/a	0.6	0.051	0.1	107
	174.0	174.1	n/a	0.1	0.012	1.9	19
	174.1	175.0	n/a	0.9	0.026	0.4	44
	175.0	175.2	n/a	0.2	0.164	4.8	576
	175.2	176.9	n/a	1.7	0.042	1.3	144
	176.9	177.2	n/a	0.3	0.035	0.9	60
	177.2	178.1	n/a	0.9	0.050	1.4	180
	179.4	180.6	n/a	1.2	0.034	0.2	19
	180.6	180.8	n/a	0.2	0.032	1.2	5
	180.8	182.1	n/a	1.3	0.019	2.7	23
	182.1	183.6	n/a	1.5	0.044	1.1	27
	183.6	184.6	n/a	1.0	0.037	1.3	22
	184.6	184.7	n/a	0.1	0.029	1.8	19
	184.7	185.1	n/a	0.4	0.020	1.1	7
	185.1	185.3	n/a	0.2	0.050	1.1	50
	185.3	186.5	n/a	1.2	0.021	1.3	48
	186.5	187.3	n/a	0.8	0.067	0.5	121
	187.3	188.0	n/a	0.7	0.045	1.9	79
	188.0	188.8	n/a	0.8	0.020	0.8	102
	188.8	189.0	n/a	0.2	0.020	2.7	149
	189.0	189.7	n/a	0.7	0.043	1.8	90
	189.7	191.0	n/a	1.3	0.092	2	155
	191.0	191.2	n/a	0.2	0.050	0.3	42
	191.2	191.6	n/a	0.4	0.068	0.4	95
	191.6	191.8	n/a	0.2	0.088	2.8	287
	191.8	192.5	n/a	0.7	0.024	0.9	33
	192.5	193.5	n/a	1.0	0.074	1.2	40



Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	195.5	196.3	n/a	0.8	0.037	3.9	761
	196.3	196.5	n/a	0.2	0.055	1.3	192
	201.7	202.4	n/a	0.7	0.035	0.5	50
	210.4	211.9	n/a	1.5	0.047	0.9	33
	211.9	212.2	n/a	0.3	0.044	0.1	33
	212.2	212.5	n/a	0.3	0.051	0.1	69
	212.5	213.6	n/a	1.1	0.066	0.8	97
	217.7	219.3	n/a	1.6	0.064	0.3	67
	221.0	221.7	n/a	0.7	0.025	0.4	22
	221.7	222.8	n/a	1.1	0.050	0.4	24
	222.8	223.0	n/a	0.2	0.034	0.5	15
	230.8	231.8	n/a	1.0	0.020	0.1	48
	240.9	242.1	n/a	1.2	0.040	0.3	75
	249.0	249.2	n/a	0.2	0.047	1.2	111
	249.2	249.9	n/a	0.7	0.051	0.1	102
	249.9	250.9	n/a	1.0	0.061	0.3	155
	252.7	254.2	n/a	1.5	0.032	0.1	34
	254.2	254.4	n/a	0.2	0.020	0.5	147
254.4 - 258.9m K-feldspar Porphyry	254.4	255.7	n/a	1.3	0.020	0.1	5
	255.7	257.3	n/a	1.6	0.026	0.1	10
	257.3	257.5	n/a	0.2	0.022	0.1	32
	257.5	258.1	n/a	0.6	0.020	0.2	11
	258.1	258.6	n/a	0.5	0.020	0.1	17
258.9 - 297.2m Greywacke/Siltstone minor Fragmental							
	266.6	266.8	n/a	0.2	0.030	0.1	89
	266.8	267.7	n/a	0.9	0.049	1	132
	267.7	268.3	n/a	0.6	0.020	0.1	120
	268.3	268.6	n/a	0.3	0.099	0.4	94
	270.1	270.2	n/a	0.1	0.058	0.3	153
	270.2	271.4	n/a	1.2	0.038	0.1	86

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	271.4	271.7	n/a	0.3	0.033	0.1	40
	281.4	281.6	n/a	0.2	0.039	0.1	126
	281.6	282.8	n/a	1.2	0.033	0.1	61
	282.8	283.5	n/a	0.7	0.049	0.1	65
	283.5	284.9	n/a	1.4	0.020	1.5	66
	286.6	288.1	n/a	1.5	0.049	0.1	73
	288.1	289.6	n/a	1.5	0.065	0.1	104
	289.6	290.4	n/a	0.8	0.167	0.1	90
<b>297.2 - 316.6m K-feldspar Porphyry</b>							
	297.7	299.0	n/a	1.3	0.027	0.1	8
	299.0	299.8	n/a	0.8	0.020	0.1	43
	299.8	300.3	n/a	0.5	0.038	0.1	66
	301.6	301.9	n/a	0.3	0.020	0.1	16
	303.0	303.6	n/a	0.6	0.036	0.1	27
	304.5	306.0	n/a	1.5	0.020	1.3	11
	306.0	306.4	n/a	0.4	0.020	0.1	10
	306.4	306.6	n/a	0.2	0.031	1.5	73
	306.6	307.1	n/a	0.5	0.020	0.1	53
	307.9	309.3	n/a	1.4	0.028	0.1	46
	309.3	309.9	n/a	0.6	0.028	0.1	44
	309.9	311.1	n/a	1.2	0.072	0.1	128
	314.5	315.5	n/a	1.0	0.039	1	263
	315.5	316.6	n/a	1.1	0.028	0.1	130
<b>316.6 - 317.9m Greywacke</b>	316.6	317.9	n/a	1.3	0.020	0.1	128
<b>317.9 - 320.5m K-feldspar Porphyry</b>	317.9	318.3	n/a	0.4	0.026	1.3	430
	320.0	320.5	n/a	0.5	0.034	1.4	198
<b>320.5 - 338.6m Greywacke</b>	320.5	320.8	n/a	0.3	0.087	3.1	279
	320.8	321.7	n/a	0.9	0.062	1	33
	324.2	325.2	n/a	1.0	0.090	0.1	26
	325.2	325.7	n/a	0.5	0.135	0.2	278

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	325.7	326.2	n/a	0.5	0.202	1.4	408
	326.6	327.7	n/a	1.1	0.364	4.5	414
	329.0	329.7	n/a	0.7	0.332	1.9	258
	334.1	334.6	n/a	0.5	0.480	1.7	197
	334.6	336.2	5372	2.0	0.145		
	336.6	338.6	5374	2.0	1.205		
338.6 - 340.2m Calcite, quartz stringer zone minor pyrite, galena	338.6	340.2	n/a	1.6	4.900	44.5	406
340.2 - 342.2m Biotite alteration envelope to stringer zone	340.2	342.2	5375	2.0	15.770		
342.2 - 342.9m Greywacke	342.2	342.9	n/a	0.7	0.191	0.3	208
342.9 - 425.3m Siltstone	342.9	343.2	n/a	0.3	0.051	0.1	46
	343.2	344.7	n/a	1.5	2.100	1.8	456
	344.7	345.3	n/a	0.6	0.202	0.1	191
	345.3	346.7	n/a	1.4	0.049	0.1	53
	346.7	348.1	n/a	1.4	0.039	0.1	27
	348.1	348.4	n/a	0.3	0.080	0.1	47
	358.1	359.9	n/a	1.8	0.072	0.1	226
	359.9	360.4	n/a	0.5	0.108	1.1	327
	360.4	361.8	n/a	1.4	0.163	0.7	335
	363.1	363.4	n/a	0.3	0.079	1.2	115
	363.4	364.7	n/a	1.3	0.116	1	206
	364.7	365.0	n/a	0.3	0.101	1.1	215
	365.0	366.5	n/a	1.5	0.121	0.9	429
	366.5	366.9	n/a	0.4	0.108	1.2	204
	377.8	378.2	n/a	0.4	0.162	1.6	256
	378.2	379.3	n/a	1.1	0.192	1.7	414
	379.3	379.7	n/a	0.4	2.072	9.4	765
	379.7	380.7	5376	1.0	0.085		
	380.7	380.8	n/a	0.1	0.562	2.1	645
	380.8	382.2	n/a	1.4	0.165	0.1	314
	382.2	382.8	n/a	0.6	0.134	0.1	227
	382.8	383.1	n/a	0.3	0.294	0.5	218
	389.5	390.1	n/a	0.6	0.251	1.9	241

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	390.1	391.6	n/a	1.5	0.481	1.7	337
	395.4	396.1	n/a	0.7	0.159	1.6	46
	396.1	396.6	n/a	0.5	0.152	0.5	199
	396.6	396.9	n/a	0.3	0.137	0.9	103
	396.9	398.6	n/a	1.7	0.134	1.2	351
	406.2	406.8	n/a	0.6	0.258	2.4	247
	406.8	407.1	n/a	0.3	0.101	1.4	95
	407.1	407.8	n/a	0.7	0.057	0.5	80
	407.8	408.8	n/a	1.0	0.053	1.3	91
	408.8	409.0	n/a	0.2	0.139	2.2	135
	415.9	416.5	n/a	0.6	0.312	2.4	732
	416.5	416.8	n/a	0.3	0.158	1.7	383
	416.8	417.1	n/a	0.3	1.900	12.6	741
	417.1	418.1	5377	1.0	0.125		
	418.1	419.5	5378	1.4	0.085		
425.3m End of Hole	419.5	421.0	n/a	1.5	0.143	1.6	310
	421.0	422.5	n/a	1.5	0.130	1.1	246

DDH 127 ASSAY (1997) TABLE							
Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
0 - 4.6m Overburden	4.6	7.6	5001	3.0	0.050		
4.6 - 144.8m Greywacke - biotite altered	7.6	8.8	5002	1.2	0.150		
occasional weak calcite biotite shears from 126.6 - 144.8m	8.8	9.6	5004	0.8	0.240	0.8	260
	9.6	10.1	5005	0.5	0.170	1.9	380
	10.1	11.2	5006	1.1	0.115	1.1	262
	11.2	13.4	5007	2.2	0.035		
	13.4	14.2	5008	0.8	0.065	1.6	147
	14.2	16.6	5009	2.4	0.035		
	16.6	18.1	5010	1.5	0.050	1.4	136
	18.1	18.4	5011	0.3	0.095	1.9	222
	18.4	18.7	5012	0.3	0.170	5.1	302
	18.7	19.8	5014	1.1	0.075	2.7	252
	19.8	20.2	5015	0.4	0.020	2.6	112
	20.2	21.0	5016	0.8	0.035		
	21.0	21.7	5017	0.7	0.080	3.4	236
	21.7	24.7	5018	3.0	0.070		
	24.7	27.7	5019	3.0	0.110		
	27.7	29.7	5020	2.0	0.100		
	29.7	31.2	5021	1.5	0.135	2.1	141
	31.2	31.6	5022	0.4	0.240	8.6	309
	31.6	33.8	5024	2.2	0.095		
	33.8	35.0	5025	1.2	0.130	3.6	230
	35.0	37.0	5026	2.0	0.065		
	37.0	38.3	5027	1.3	0.160	3.0	197
	38.3	39.1	5028	0.8	0.095	3.8	381
	39.1	39.6	5029	0.5	0.060	3.4	323
	39.6	42.6	5030	3.0	0.060		
	42.6	45.6	5031	3.0	0.115		
	45.6	48.8	5032	3.2	0.150		
	48.8	49.6	5034	0.8	0.420	5.8	354
	49.6	50.3	5035	0.7	0.170	3.6	225
	50.3	51.9	5036	1.6	0.090	3.8	143
	51.9	52.5	5037	0.6	0.030	1.8	59
	52.5	52.8	5038	0.3	0.080	0.8	48
	52.8	53.1	5039	0.3	0.060	1.3	29
	53.1	54.1	5040	1.0	0.035	1.2	21
	54.1	54.8	5041	0.7	0.145	2.5	140
	54.8	57.8	5042	3.0	0.500		

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	57.8	59.2	5044	1.4	0.160	3.0	284
	59.2	60.5	5045	1.3	0.590	3.6	242
	60.5	61.3	5046	0.8	3.440		
	61.3	61.5	5047	0.2	0.435	6.9	411
	61.5	62.3	5048	0.8	1.735		
	62.3	65.3	5049	3.0	0.590		
	65.3	68.3	5050	3.0	0.275		
	68.3	69.4	5051	1.1	0.090		
	69.4	69.6	5052	0.2	0.235	1.4	269
	69.6	70.9	5054	1.3	0.180		
	70.9	71.6	5055	0.7	0.145	2.1	115
	71.6	73.1	5056	1.5	0.250	1.0	80
	73.1	76.1	5057	3.0	0.095		
	76.1	79.1	5058	3.0	0.090		
	79.1	80.8	5059	1.7	0.065		
	80.8	81.0	5060	0.2	0.085	3.4	202
	81.0	84.2	5061	3.2	0.030		
	84.2	84.5	5062	0.3	0.010	1.4	92
	84.5	85.5	5064	1.0	0.125	3.4	173
	85.5	85.8	5065	0.3	0.660	4.9	55
	85.8	86.5	5066	0.7	0.250	4.1	201
	86.5	88.0	5067	1.5	0.095	4.1	201
	88.0	91.0	5068	3.0	0.050		
	91.0	94.0	5069	3.0	0.060		
	94.0	94.9	5070	0.9	0.040		
	94.9	96.4	5071	1.5	0.170	1.6	279
	96.4	99.4	5072	3.0	0.205		
	99.4	102.4	5074	3.0	0.180		
	102.4	104.2	5075	1.8	0.235		
	104.2	105.4	5076	1.2	0.250	1.2	99
	105.4	106.2	5077	0.8	0.285	3.4	100
	106.2	106.5	5078	0.3	0.075	1.6	102
	106.5	109.5	5079	3.0	0.220		
	109.5	110.8	5080	1.3	0.180		
	110.8	112.3	5081	1.5	0.085	2.1	76
	112.3	112.5	5082	0.2	0.005	1.2	38
	112.5	113.7	5084	1.2	0.005	1.5	17
	113.7	114.3	5085	0.6	0.010	0.1	95
	114.3	115.5	5086	1.2	0.065	0.5	84

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	115.5	117.0	5087	1.5	0.100	1.0	84
	117.0	117.6	5088	0.6	0.220	4.8	139
	117.6	118.6	5089	1.0	0.075	1.1	57
	118.6	120.7	5090	2.1	0.115	0.8	197
	120.7	122.9	5091	2.2	0.155		
	122.9	124.3	5092	1.4	0.190	2.7	154
	124.3	124.6	5094	0.3	0.345	4.4	36
	124.6	126.6	5095	2.0	0.175	2.6	197
	126.6	128.2	5096	1.6	0.565		
	128.2	131.2	5097	3.0	0.630		
	131.2	134.2	5098	3.0	0.320		
	134.2	135.5	5099	1.3	0.170		
	135.5	135.7	5100	0.2	0.185	2.1	227
	135.7	138.7	5101	3.0	0.640		
	138.7	141.7	5102	3.0	0.450		
	141.7	144.6	5104	2.9	0.285		
	144.6	144.8	5105	0.2	0.320	4.3	273
144.8 - 192.1m Siltstone/Greywacke - moderate sericite alteration 2-3% pyrite, locally 5-7% pyrite	144.8	146.9	5106	2.1	0.200		
	146.9	147.6	5107	0.7	0.280	3.2	309
	147.6	148.0	5108	0.4	1.040	60.9	117
	148.0	148.3	5109	0.3	0.800	4.8	53
	148.3	150.3	5110	2.0	0.200		
	150.3	151.7	5111	1.4	0.230		
	151.7	152.3	5112	0.6	4.200	6.7	428
	152.3	153.8	5114	1.5	1.095		
	153.8	154.0	5115	0.2	0.350	2.3	237
	154.0	155.6	5116	1.6	0.315	2.1	664
	155.6	156.6	5117	1.0	0.280	2.1	237
	156.6	157.5	5118	0.9	0.485	3.1	664
	157.5	158.9	5119	1.4	0.760	2.1	279
	158.9	161.0	5120	2.1	0.200		
	161.0	162.5	5121	1.5	0.370	2.5	398
	162.5	163.0	5122	0.5	0.120	1.9	55
	163.0	164.2	5124	1.2	0.125	1.1	256
	164.2	164.6	5125	0.4	0.705	17.7	1015
	164.6	167.6	5126	3.0	0.560		
	167.6	170.6	5127	3.0	0.410		
	170.6	172.6	5128	2.0	0.440		
	172.6	173.1	5129	0.5	0.420	4.7	709

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	173.1	174.1	5130	1.0	0.245	3.5	456
	174.1	176.2	5131	2.1	0.170		
	176.2	176.4	5132	0.2	0.030	0.4	32
	176.4	177.9	5134	1.5	0.020	1.0	38
	177.9	178.7	5135	0.8	0.160		
	178.7	179.0	5136	0.3	0.410	2.2	10
	179.0	180.6	5137	1.6	1.560	1.6	175
	180.6	181.0	5138	0.4	0.125	1.5	25
	181.0	181.2	5139	0.2	0.075	1.7	10
	181.2	181.7	5140	0.5	0.060		
	181.7	183.2	5141	1.5	0.075	0.8	117
	183.2	183.4	5142	0.2	0.100	1.7	19
	183.4	186.4	5144	3.0	0.085		
	186.4	189.4	5145	3.0	0.130		
	189.4	192.4	5146	3.0	0.070		
192.1 - 461.9m Siltstone minor Greywacke - moderate to intense sericite alteration. Pyrite 1 to 7% with minor sphalerite especially from 196.2 - 287.3m	192.4	195.4	5147	3.0	0.115		
	195.4	195.9	5148	0.5	0.060		
	195.9	196.2	5149	0.3	0.160	15.9	88
	196.2	197.7	5150	1.5	0.950	4.5	465
	197.7	200.5	5151	2.8	0.100		
	200.5	201.7	5152	1.2	0.190	11.5	356
	201.7	202.4	5154	0.7	0.325	7.4	136
	202.4	203.0	5155	0.6	0.400	7.0	1492
	203.0	206.0	5156	3.0	0.595		
	206.0	206.8	5157	0.8	0.475		
	206.8	207.0	5158	0.2	0.280	3.9	163
	207.0	208.5	5159	1.5	0.250	1.9	87
	208.5	211.5	5160	3.0	0.160		
	211.5	214.5	5161	3.0	0.210		
	214.5	216.3	5162	1.8	1.150		
	216.3	216.7	5164	0.4	1.260	15.6	1193
	216.7	217.3	5165	0.6	0.230	10.9	702
	217.3	217.6	5166	0.3	0.900	7.7	1195
	217.6	218.0	5167	0.4	0.295	1.9	341
	218.0	221.0	5168	3.0	0.185		
	221.0	221.5	5169	0.5	0.095		
	221.5	223.0	5170	1.5	0.665	0.6	96
	223.0	223.4	5171	0.4	0.705	0.9	32
	223.4	224.6	5172	1.2	2.880	1.8	315



Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	224.6	227.6	5174	3.0	0.220		
	227.6	230.6	5175	3.0	0.205		
	230.6	233.6	5176	3.0	0.380		
	233.6	235.5	5177	1.9	0.170		
	235.5	236.9	5178	1.4	0.315	2.8	402
	236.9	237.2	5179	0.3	1.155	5.0	1547
	237.2	237.4	5180	0.2	0.185	1.8	151
	237.4	238.9	5181	1.5	0.100	5.2	94
	238.9	241.9	5182	3.0	0.210		
	241.9	242.5	5184	0.6	0.435		
	242.5	242.9	5185	0.4	1.800	1.8	149
	242.9	243.1	5186	0.2	0.340	18.5	131
	243.1	243.8	5187	0.7	0.370	33.1	288
	243.8	246.8	5188	3.0	0.325		
	246.8	249.8	5189	3.0	0.185		
	249.8	252.8	5190	3.0	0.335		
	252.8	255.8	5191	3.0	0.195		
	255.8	256.7	5192	0.9	0.140		
	256.7	257.8	5194	1.1	0.120	41.8	113
	257.8	258.1	5195	0.3	0.520	2.7	76
	258.1	259.3	5196	1.2	0.245	9.5	105
	259.3	259.5	5197	0.2	0.750	7.5	315
	259.5	262.6	5198	3.1	0.180		
	262.6	262.9	5199	0.3	1.920	50.9	1528
	262.9	263.8	5200	0.9	0.305	22.6	184
	263.8	264.0	5201	0.2	0.070	1.6	43
	264.0	265.4	5202	1.4	0.065		
	265.4	265.8	5204	0.4	0.040	0.3	50
	265.8	266.8	5205	1.0	0.140	0.8	290
	266.8	269.8	5206	3.0	0.380		
	269.8	272.8	5207	3.0	0.195		
	272.8	274.1	5208	1.3	0.205		
	274.1	275.6	5209	1.5	0.200	1.7	155
	275.6	278.6	5210	3.0	1.185		
	278.6	280.5	5211	1.9	2.290		
	280.5	281.8	5212	1.3	0.465	2.2	904
	281.8	284.8	5214	3.0	0.500		
	284.8	285.8	5215	1.0	0.145		
	285.8	286.0	5216	0.2	0.650	1.5	783

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	286.0	287.3	5217	1.3	0.260	1.4	181
	287.3	290.3	5218	3.0	0.150		
	290.3	293.3	5219	3.0	0.130		
	293.3	294.3	5220	1.0	0.180		
	294.3	295.3	5221	1.0	0.070	0.1	170
	295.3	295.5	5222	0.2	0.070	1.4	77
	295.5	298.5	5224	3.0	0.110		
	298.5	299.2	5225	0.7	0.075		
	299.2	300.5	5226	1.3	0.140	0.2	382
	300.5	300.6	5227	0.1	0.030	0.5	61
	300.6	303.6	5228	3.0	0.090		
	303.6	305.1	5229	1.5	0.100		
	305.1	306.1	5230	1.0	0.065	1.8	262
	306.1	309.1	5231	3.0	0.090		
	309.1	309.6	5232	0.5	0.045		
	309.6	310.4	5234	0.8	0.050	1.4	27
	310.4	312.0	5235	1.6	0.070	0.4	74
	312.0	313.9	5236	1.9	0.035		
	313.9	315.0	5237	1.1	0.055	1.3	173
	315.0	315.5	5238	0.5	0.035	0.8	236
	315.5	317.0	5239	1.5	0.025	1.5	162
	317.0	320.0	5240	3.0	0.110		
	320.0	321.3	5241	1.3	0.025		
	321.3	321.9	5242	0.6	0.060	1.1	81
	321.9	324.3	5244	2.4	0.030		
	324.3	324.7	5245	0.4	0.025	1.6	138
	324.7	326.2	5246	1.5	0.020	0.6	139
	326.2	326.3	5247	0.1	0.035	3.3	81
	326.3	329.3	5248	3.0	0.025		
	329.3	330.0	5249	0.7	0.035		
	330.0	330.1	5250	0.1	0.120	2.3	23
	330.1	333.1	5251	3.0	0.040		
	333.1	334.1	5252	1.0	0.055		
	334.1	335.9	5254	1.8	0.015	1.7	132
	335.9	337.1	5255	1.2	0.020		
	337.1	337.4	5256	0.3	0.030	1.6	185
	337.4	338.8	5257	1.4	0.040	2.1	450
	338.8	341.8	5258	3.0	0.020		
	341.8	344.8	5259	3.0	0.015		

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	344.8	346.4	5260	1.6	0.010		
	346.4	347.8	5261	1.4	0.015	0.8	41
	347.8	349.2	5262	1.4	0.030	0.2	101
	349.2	349.9	5264	0.7	0.050	0.1	250
	349.9	352.9	5265	3.0	0.035		
	352.9	355.5	5266	2.6	0.030		
	355.5	357.0	5267	1.5	0.065	1.7	217
	357.0	357.3	5268	0.3	0.005	1.1	399
	357.3	358.6	5269	1.3	0.255	2.8	615
	358.6	361.8	5270	3.2	0.050		
	361.8	363.3	5271	1.5	0.050	1.9	241
	363.3	364.2	5272	0.9	0.055	1.5	297
	364.2	367.2	5274	3.0	0.185		
	367.2	370.2	5275	3.0	0.160		
	370.2	373.1	5276	2.9	0.180		
	373.1	373.4	5277	0.3	0.080	7.4	730
	373.4	374.2	5278	0.8	0.125	1.4	346
	374.2	374.6	5279	0.4	0.425	1.3	265
	374.6	374.9	5280	0.3	0.110	1.4	287
	374.9	376.7	5281	1.8	0.055		
	376.7	376.9	5282	0.2	0.005	5.5	199
	376.9	378.4	5284	1.5	0.095	1.3	136
	378.4	381.4	5285	3.0	0.040		
	381.4	384.4	5286	3.0	0.025		
	384.4	387.4	5287	3.0	0.025		
	387.4	390.2	5288	2.8	0.020		
	390.2	391.8	5289	1.6	0.025	2.2	148
	391.8	394.8	5290	3.0	0.030		
	394.8	397.8	5291	3.0	0.030		
	397.8	400.8	5292	3.0	0.020		
	400.8	402.7	5294	1.9	0.020		
	402.7	404.2	5295	1.5	0.015	2.4	85
	404.2	405.7	5296	1.5	0.015	1.6	151
	405.7	408.5	5297	2.8	0.025		
	408.5	410.1	5298	1.6	0.030	2.6	251
	410.1	410.3	5299	0.2	0.130	1.4	161
	410.3	413.3	5300	3.0	0.040		
	413.3	414.4	5301	1.1	0.080		
	414.4	415.9	5302	1.5	0.120	2.6	628

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	415.9	416.1	5304	0.2	0.025	2.0	196
	416.1	417.6	5305	1.5	0.035	1.7	477
	417.6	421.0	5306	3.4	0.070		
	421.0	421.2	5307	0.2	0.240	1.5	210
	421.2	422.8	5308	1.6	0.045	1.1	441
	422.8	425.9	5309	3.1	0.060		
	425.9	427.4	5310	1.5	0.050	1.7	342
	427.4	428.1	5311	0.7	0.060	1.6	405
	428.1	428.4	5312	0.3	0.090	0.9	405
	428.4	431.2	5314	2.8	0.110		
	431.2	432.9	5315	1.7	0.080	1.7	506
	432.9	435.9	5316	3.0	0.065		
	435.9	438.9	5317	3.0	0.320		
	438.9	441.9	5318	3.0	0.090		
	441.9	443.8	5319	1.9	0.020		
	443.8	444.1	5320	0.3	0.020	4.8	90
	444.1	445.8	5321	1.7	0.010	0.8	40
	445.8	446.6	5322	0.8	0.080	1.8	471
	446.6	448.6	5324	2.0	0.040		
	448.6	450.2	5325	1.6	0.030	1.3	862
	450.2	450.5	5326	0.3	0.040	0.6	282
	450.5	450.8	5327	0.3	0.025	9.5	204
	450.8	453.8	5328	3.0	0.030		
	453.8	454.5	5329	0.7	0.045		
	454.5	456.0	5330	1.5	0.040	1.5	359
	456.0	456.2	5331	0.2	0.025	1.3	177
	456.2	459.1	5332	2.9	0.050		
	459.1	460.8	5334	1.7	0.040	1.2	471
461.9m End of Hole	460.8	461.9	5335	1.1	0.065	1.5	433

DDH 129 ASSAY (1997) TABLE							
Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
0 - 141.25m Greywacke - weak biotite alteration	3.5	4.5	7194	1.0	0.010		
trace disseminated pyrite	4.5	4.7	7195	0.2	0.120	5.3	115
	4.7	5.5	7196	0.8	0.015	0.9	65
	5.5	6.3	7197	0.8	0.005	0.3	62
	6.3	6.4	7198	0.1	0.020	2.3	526
	6.4	7.5	7199	1.1	0.015	0.7	136
	7.5	9.0	7200	1.5	0.025	0.4	95
	9.0	9.9	7201	0.9	0.020	0.4	140
	9.9	10.3	7202	0.4	0.015	45.4	289
	10.3	11.5	7204	1.2	0.020	0.1	130
	11.5	14.5	7205	3.0	0.040		
	14.5	17.5	7206	3.0	0.030		
	17.5	20.5	7207	3.0	0.045		
	20.5	23.5	7208	3.0	0.055		
	23.5	26.5	7209	3.0	0.050		
	26.5	29.5	7210	3.0	0.065		
	29.5	30.0	7211	0.5	0.035		
	30.0	31.1	7212	1.1	0.010	0.5	66
	31.1	31.2	7214	0.1	0.175	2.3	131
	31.2	32.0	7215	0.8	0.020	0.1	90
	32.0	35.0	7216	3.0	0.075		
	35.0	38.0	7217	3.0	0.045		
	38.0	41.0	7218	3.0	0.140		
	41.0	41.5	7219	0.5	0.100		
	41.5	42.3	7220	0.8	0.225	0.2	26
	42.3	42.8	7221	0.5	2.740	1.4	390
	42.8	43.5	7222	0.7	2.340	0.1	231
	43.5	46.5	7224	3.0	0.110		
	46.5	49.5	7225	3.0	0.045		
	49.5	50.0	7226	0.5	0.310		
	50.0	51.0	7227	1.0	0.060	1.0	108
	51.0	52.0	7228	1.0	0.035	0.1	97
	52.0	55.0	7229	3.0	0.025		
	55.0	56.0	7230	1.0	0.020		
	56.0	57.1	7231	1.1	0.010	0.3	70
	57.1	57.8	7232	0.7	0.030	2.7	70
	57.8	57.9	7234	0.1	0.150	2.4	169
	57.9	59.0	7235	1.1	0.035	2.1	103

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	59.0	62.0	7236	3.0	0.030		
	62.0	65.0	7237	3.0	0.050		
	65.0	68.0	7238	3.0	0.050		
	68.0	70.0	7239	2.0	0.065		
	70.0	71.1	7240	1.1	0.580	2.1	101
	71.1	71.6	7241	0.5	0.710	9.1	432
	71.6	74.6	7242	3.0	0.330		
	74.6	77.5	7244	2.9	0.050		
	77.5	77.6	7245	0.1	0.115	2.9	268
	77.6	80.6	7246	3.0	0.290		
	80.6	83.6	7247	3.0	0.110		
	83.6	85.9	7248	2.3	0.460		
	85.9	87.0	7249	1.1	0.175	4.9	179
	87.0	88.4	7250	1.4	0.555	3.3	392
	88.4	88.7	7251	0.3	0.265	4.9	243
	88.7	88.9	7252	0.2	0.525	6.9	353
	88.9	89.6	7254	0.7	0.195	6.0	181
	89.6	90.0	7255	0.4	0.155	4.2	435
	90.0	93.0	7256	3.0	0.205		
	93.0	94.2	7257	1.2	0.310		
	94.2	95.1	7258	0.9	0.530	2.6	507
	95.1	98.1	7259	3.0	0.240		
	98.1	99.1	7260	1.0	0.210		
	99.1	100.8	7261	1.7	0.480	4.9	283
	100.8	102.0	7262	1.2	0.265	6.2	329
	102.0	103.1	7264	1.1	0.210	68.1	178
	103.1	103.8	7265	0.7	0.345	12.0	213
	103.8	104.0	7266	0.2	0.085	4.3	292
	104.0	105.2	7267	1.2	0.205	2.2	121
	105.2	108.2	7268	3.0	0.080		
	108.2	110.0	7269	1.8	0.090		
	110.0	111.6	7270	1.6	0.070	2.8	251
	111.6	112.4	7271	0.8	0.070	2.9	326
	112.4	113.5	7272	1.1	0.190	2.0	274
	113.5	115.2	7274	1.7	0.140	2.2	302
	115.2	118.0	7275	2.8	0.140		
	118.0	121.0	7276	3.0	0.200		
	121.0	124.0	7277	3.0	0.170		
	124.0	126.0	7278	2.0	0.135		

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	126.0	127.1	7279	1.1	0.190	8.0	185
	127.1	127.5	7280	0.4	0.020	2.6	22
	127.5	127.6	7281	0.1	0.045	9.1	327
	127.6	128.5	7282	0.9	0.010	1.6	19
	128.5	129.4	7284	0.9	0.050	2.3	96
	129.4	129.5	7285	0.1	0.305	9.9	277
	129.5	130.5	7286	1.0	0.260	20.5	123
	130.5	132.1	7287	1.6	0.100	2.5	135
	132.1	133.0	7288	0.9	0.080	2.3	74
	133.0	136.0	7289	3.0	0.350		
	136.0	139.0	7290	3.0	0.200		
	139.0	140.0	7291	1.0	0.090		
141.25 - 141.5m Basalt dyke	140.0	141.3	7292	1.3	0.195	3.9	108
141.5 -148.9m Volcanic Fragmental	141.3	141.5	7294	0.2	0.225	3.2	187
	141.5	143.0	7295	1.5	0.270	3.1	81
	143.0	146.0	7296	3.0	0.170		
148.9 - 209.7m Greywacke - increasing quartz, sericite, pyrite alteration	146.0	149.0	7297	3.0	0.660		
	149.0	150.5	7298	1.5	0.425		
	150.5	151.8	7299	1.3	0.265	2.5	98
	151.8	152.8	7300	1.0	0.580	5.1	203
	152.8	153.7	7301	0.9	0.865	3.7	182
	153.7	154.2	7302	0.5	0.430	4.3	270
	154.2	156.1	7304	1.9	0.185	4.0	336
	156.1	156.7	7305	0.6	1.660	16.5	3497
	156.7	159.7	7306	3.0	1.030		
	159.7	162.7	7307	3.0	0.735		
	162.7	164.0	7308	1.3	0.270		
	164.0	165.5	7309	1.5	0.520	5.3	179
	165.5	166.9	7310	1.4	0.610	2.8	67
	166.9	167.5	7311	0.6	0.680	2.1	102
	167.5	169.0	7312	1.5	0.450	2.9	153
	169.0	172.0	7314	3.0	0.520		
	172.0	173.5	7315	1.5	0.900		
	173.5	175.1	7316	1.6	0.270	5.2	301
	175.1	175.2	7317	0.1	0.250	2.3	23
	175.2	176.5	7318	1.3	0.260	3.2	103
	176.5	178.5	7319	2.0	0.280	5.1	71
	178.5	181.1	7320	2.6	0.120	1.7	15
	181.1	181.8	7321	0.7	0.340	1.9	17

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	181.8	182.8	7322	1.0	0.200	3.3	124
	182.8	184.0	7324	1.2	0.260	3.8	121
	184.0	185.5	7325	1.5	0.180	3.6	40
	185.5	188.5	7326	3.0	0.230		
	188.5	191.5	7327	3.0	0.150		
	191.5	194.5	7328	3.0	0.155		
	194.5	196.0	7329	1.5	0.090		
	196.0	197.3	7330	1.3	0.160	4.1	447
	197.3	197.6	7331	0.3	4.920	489.0	2268
	197.6	199.0	7332	1.4	0.800	9.4	765
	199.0	200.5	7334	1.5	1.000	3.5	906
	200.5	202.0	7335	1.5	0.460	3.9	364
	202.0	203.3	7336	1.3	0.170	2.5	91
	203.3	204.2	7337	0.9	5.160	76.2	2446
	204.2	206.0	7338	1.8	0.485	4.4	489
	206.0	207.5	7339	1.5	0.890	3.0	366
	207.5	209.0	7340	1.5	0.360	3.3	369
	209.0	209.7	7341	0.7	0.590	2.6	69
209.7 - 248.2m Volcanic Fragmental - intense quartz, sericite, pyrite alteration	209.7	210.0	7342	0.3	0.800	2.6	58
	210.0	211.5	7344	1.5	0.080	2.0	43
	211.5	213.0	7345	1.5	0.120	2.1	188
	213.0	215.0	7346	2.0	0.305	2.2	479
	215.0	218.0	7347	3.0	0.440		
	218.0	221.0	7348	3.0	0.450		
	221.0	224.0	7349	3.0	0.390		
	224.0	227.0	7350	3.0	0.360		
	227.0	227.5	7351	0.5	0.360		
	227.5	229.0	7352	1.5	0.325	2.4	189
	229.0	229.2	7354	0.2	0.500	2.4	189
	229.2	230.5	7355	1.3	0.230	1.3	196
	230.5	233.5	7356	3.0	0.480		
	233.5	236.5	7357	3.0	0.895		
	236.5	239.5	7358	3.0	0.370		
	239.5	242.5	7359	3.0	0.460		
	242.5	244.0	7360	1.5	0.955		
	244.0	245.5	7361	1.5	1.320		
	245.5	247.0	7362	1.5	0.220	2.0	224
	247.0	247.9	7364	0.9	0.420	7.8	300
	247.9	248.2	7365	0.3	0.590	7.8	300



Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
248.2 - 368.1m Greywacke - intense quartz, sericite, pyrite alteration	248.2	250.0	7366	1.8	0.180	2.0	138
disseminated pyrite increasing 3- 15%	250.0	251.5	7367	1.5	0.170	1.9	202
	251.5	252.7	7368	1.2	0.095	1.0	388
	252.7	252.9	7369	0.2	1.515	7.0	199
	252.9	254.5	7370	1.6	0.375	3.0	354
	254.5	257.5	7371	3.0	0.775		
	257.5	260.5	7372	3.0	0.100		
	260.5	261.9	7374	1.4	0.100	1.8	78
	261.9	262.0	7375	0.1	1.400	4.8	274
	262.0	263.5	7376	1.5	0.080	1.8	156
	263.5	265.0	7377	1.5	0.655	2.0	108
	265.0	266.2	7378	1.2	0.185	2.7	99
	266.2	266.6	7379	0.4	2.250	10.7	263
	266.6	267.8	7380	1.2	0.200	3.1	221
	267.8	268.2	7381	0.4	2.010	1.2	56
	268.2	268.6	7382	0.4	0.045	1.6	111
	268.6	270.0	7384	1.4	0.050	0.9	147
	270.0	271.5	7385	1.5	0.080	8.2	230
	271.5	273.0	7386	1.5	0.095	1.9	72
	273.0	276.0	7387	3.0	0.210		
	276.0	279.0	7388	3.0	0.060		
	279.0	281.0	7389	2.0	0.085		
	281.0	282.0	7390	1.0	0.100	2.6	39
	282.0	283.5	7391	1.5	0.155	1.0	59
	283.5	284.9	7392	1.4	0.130	1.8	52
	284.9	285.1	7394	0.2	0.145	1.5	42
	285.1	286.5	7395	1.4	0.070	2.8	57
	286.5	288.0	7396	1.5	0.250	2.0	56
	288.0	289.0	7397	1.0	0.110	3.6	162
	289.0	292.0	7398	3.0	0.065		
	292.0	293.4	7399	1.4	0.040		
	293.4	294.6	7400	1.2	0.150	2.4	171
	294.6	296.5	7401	1.9	0.290	2.1	96
	296.5	298.0	7402	1.5	0.230	1.8	83
	298.0	299.0	7404	1.0	0.270	1.0	85
	299.0	299.9	7405	0.9	0.430	2.3	43
	299.9	301.2	7406	1.3	0.130	2.4	89
	301.2	302.5	7407	1.3	0.075	1.2	84
	302.5	304.0	7408	1.5	0.070	1.6	70

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	304.0	304.8	7409	0.8	0.090	2.1	80
	304.8	305.3	7410	0.5	0.170	1.3	70
	305.3	306.5	7411	1.2	0.125	4.0	138
	306.5	308.0	7412	1.5	0.140	3.7	271
	308.0	311.0	7414	3.0	0.105		
	311.0	314.0	7415	3.0	0.325		
	314.0	317.0	7416	3.0	0.405		
	317.0	320.0	7417	3.0	0.165		
	320.0	320.5	7418	0.5	0.110		
	320.5	321.5	7419	1.0	0.120	4.0	28
	321.5	322.5	7420	1.0	0.060	2.7	28
	322.5	323.5	7421	1.0	0.045	1.4	19
	323.5	324.5	7422	1.0	0.050	1.2	17
	324.5	327.5	7424	3.0	0.080		
	327.5	330.5	7425	3.0	0.115		
	330.5	333.5	7426	3.0	0.135		
	333.5	336.5	7427	3.0	0.140		
	336.5	339.5	7428	3.0	0.145		
	339.5	342.5	7429	3.0	0.130		
	342.5	345.5	7430	3.0	0.110		
	345.5	348.5	7431	3.0	0.070		
	348.5	351.5	7432	3.0	0.125		
	351.5	354.5	7434	3.0	0.365		
	354.5	355.0	7435	0.5	0.210		
	355.0	356.0	7436	1.0	0.060	1.7	115
	356.0	357.5	7437	1.5	0.055	0.1	72
	357.5	357.7	7438	0.2	2.210	8.7	203
	357.7	359.0	7439	1.3	0.070	2.0	77
	359.0	362.0	7440	3.0	0.160		
	362.0	364.0	7441	2.0	0.140		
	364.0	365.0	7442	1.0	0.455	7.2	589
	365.0	366.0	7444	1.0	0.125	2.9	90
	366.0	366.9	7445	0.9	0.170	1.4	263
	366.9	367.3	7446	0.4	1.270	23.3	211
	367.3	368.1	7447	0.8	0.275	4.2	293
368.1 - 382.6m Siltstone - intense quartz, sericite, pyrite alteration	368.1	369.0	7448	0.9	0.115	0.7	347
core highly broken	369.0	370.0	7449	1.0	0.080	0.9	311
	370.0	373.0	7450	3.0	0.110		
	373.0	376.0	7451	3.0	0.120		

## C129\_97.XLS

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	376.0	379.0	7452	3.0	0.270		
	379.0	382.0	7454	3.0	0.210		
382.6m End of Hole	382.0	382.6	7455	0.6	0.075		

DDH 130 ASSAY (1997) TABLE							
Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
0- 36.5m Greywacke - weak biotite alteration	4.6	5.0	7029	0.4	0.010		
	5.0	6.0	7030	1.0	0.035	1.3	155
	6.0	6.2	7031	0.2	0.010	2.8	101
	6.2	7.0	7032	0.8	0.030	0.4	145
	7.0	10.0	7034	3.0	0.025		
	10.0	13.0	7035	3.0	0.035		
	13.0	16.0	7036	3.0	0.025		
	16.0	19.0	7037	3.0	0.030		
	19.0	21.0	7038	2.0	0.020		
	21.0	24.0	7039	3.0	0.060		
	24.0	27.0	7040	3.0	0.025		
	27.0	30.0	7041	3.0	0.030		
	30.0	33.0	7042	3.0	0.035		
	33.0	35.0	7044	2.0	0.040		
	35.0	36.4	7045	1.4	0.050	1.4	56
	36.4	36.5	7046	0.1	0.065	1.3	77
36.5- 37.5m Basalt Dyke	36.5	37.0	7047	0.5	0.055	0.8	23
37.5 - 48.8m Greywacke - as above	37.0	37.4	7048	0.4	0.070	0.7	13
	37.4	38.0	7049	0.6	0.040	0.7	29
	38.0	41.0	7050	3.0	0.120		
	41.0	44.0	7051	3.0	0.150		
	44.0	45.4	7052	1.4	0.060		
	45.4	45.6	7054	0.2	0.135	2.5	434
	45.6	45.8	7055	0.2	2.580	4.6	535
	45.8	46.5	7056	0.7	0.055	1.8	176
	46.5	48.0	7057	1.5	0.025	43.1	18
	48.0	48.8	7058	0.8	0.030	0.5	73
48.8 -49.15m Basalt Dyke	48.8	49.2	7059	0.4	0.050	0.6	59
49.15 - 72.3m Greywacke - as above	49.2	50.0	7060	0.8	0.020	0.1	100
	50.0	51.2	7061	1.2	0.010	0.6	183
	51.2	52.5	7062	1.3	0.005	0.1	49
	52.5	55.5	7064	3.0	0.010		
	55.5	58.5	7065	3.0	0.050		
	58.5	61.5	7066	3.0	0.070		
	61.5	65.0	7067	3.5	0.515		
	65.0	65.9	7068	0.9	0.065	2.6	156
	65.9	66.4	7069	0.5	0.025	1.6	122
	66.4	66.5	7070	0.1	0.075	10.5	67

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	66.5	67.6	7071	1.1	0.330	0.2	35
	67.6	67.7	7072	0.1	0.170	2.5	312
	67.7	69.1	7074	1.4	0.070	1.0	89
	69.1	69.3	7075	0.2	0.945	5.6	69
	69.3	70.5	7076	1.2	0.125	4.6	184
	70.5	71.0	7077	0.5	0.310	7.5	82
	71.0	71.8	7078	0.8	1.330	7.1	105
	71.8	72.3	7079	0.5	3.460	13.9	3078
72.3 -72.45m Massive Pyrite, Chalcopyrite, Arsenopyrite Vein	72.3	72.5	7080	0.2	39.220	160.7	1530
72.45 - 162.1m Greywacke - quartz, sericite, pyrite alteration increasing moderate alteration starting 111.0m	72.5	74.0	7081	1.5	0.215	4.9	437
	74.0	75.5	7082	1.5	0.495	4.0	102
	75.5	76.2	7084	0.7	0.105	1.1	80
	76.2	77.7	7085	1.5	0.065	2.1	118
	77.7	77.9	7086	0.2	0.025	0.5	80
	77.9	80.9	7087	3.0	0.095		
	80.9	83.9	7088	3.0	0.110		
	83.9	86.9	7089	3.0	0.060		
	86.9	89.9	7090	3.0	0.040		
	89.9	92.9	7091	3.0	0.050		
	92.9	96.0	7092	3.1	0.430		
	96.0	97.1	7094	1.1	0.075	1.9	158
	97.1	98.0	7095	0.9	0.065	1.6	225
	98.0	99.3	7096	1.3	0.035	2.4	182
	99.3	99.8	7097	0.5	0.380	6.4	223
	99.8	101.0	7098	1.2	0.055	2.3	106
	101.0	102.0	7099	1.0	0.095	3.0	202
	102.0	102.2	7100	0.2	0.180	2.7	417
	102.2	103.2	7101	1.0	0.105	2.4	242
	103.2	103.6	7102	0.4	0.205	2.9	90
	103.6	104.0	7104	0.4	0.160	1.5	169
	104.0	107.0	7105	3.0	0.260		
	107.0	110.0	7106	3.0	0.300		
	110.0	111.0	7107	1.0	0.110		
	111.0	112.5	7108	1.5	0.650	5.5	12
	112.5	113.7	7109	1.2	0.355	4.2	319
	113.7	113.9	7110	0.2	0.525	6.2	32
	113.9	114.7	7111	0.8	0.540	5.8	120
	114.7	115.1	7112	0.4	0.235	2.6	117
	115.1	116.0	7114	0.9	0.150	3.8	188

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	116.0	116.4	7115	0.4	0.450	5.4	289
	116.4	117.0	7116	0.6	0.185	4.5	117
	117.0	118.0	7117	1.0	0.390	4.2	272
	118.0	121.0	7118	3.0	0.430		
	121.0	122.0	7119	1.0	0.765		
	122.0	122.9	7120	0.9	0.150	11.3	468
	122.9	123.2	7121	0.3	0.340	6.3	13
	123.2	124.5	7122	1.3	0.710	4.6	119
	124.5	125.2	7124	0.7	1.115	10.8	158
	125.2	125.5	7125	0.3	0.585	13.9	872
	125.5	126.5	7126	1.0	0.655	5.9	219
	126.5	128.0	7127	1.5	1.030	12.2	197
	128.0	129.4	7128	1.4	0.155	4.7	306
	129.4	129.8	7129	0.4	0.250	7.7	54
	129.8	131.0	7130	1.2	0.240	5.3	291
	131.0	132.5	7131	1.5	0.255	8.7	491
	132.5	133.5	7132	1.0	0.335	4.5	378
	133.5	135.1	7134	1.6	0.400	8.2	174
	135.1	136.0	7135	0.9	0.220	3.7	315
	136.0	137.6	7136	1.6	0.190	78.0	160
	137.6	140.6	7137	3.0	0.305		
	140.6	143.6	7138	3.0	0.680		
	143.6	146.6	7139	3.0	0.240		
	146.6	149.6	7140	3.0	0.205		
	149.6	151.0	7141	1.4	0.135		
	151.0	152.1	7142	1.1	0.260	1.4	130
	152.1	152.8	7144	0.7	0.120	0.5	29
	152.8	154.0	7145	1.2	0.130	2.1	15
	154.0	155.7	7146	1.7	0.280	100.5	85
	155.7	157.0	7147	1.3	0.605	74.2	95
	157.0	158.5	7148	1.5	0.300	54.9	101
	158.5	160.0	7149	1.5	0.490	5.4	182
	160.0	161.5	7150	1.5	2.320	4.1	281
162.1 - 233.2 Siltstone - moderate quartz, sericite, pyrite alteration becoming intense at 175.0m	161.5	162.7	7151	1.2	0.425	2.5	361
	162.7	164.0	7152	1.3	0.270	2.2	5
	164.0	167.0	7154	3.0	0.255		
	167.0	170.0	7155	3.0	0.535		
	170.0	173.0	7156	3.0	0.575		
	173.0	176.0	7157	3.0	0.815		

Drill log summary	From m	To m	Number	Width m	Au ppm	Ag ppm	Cu ppm
	176.0	179.0	7158	3.0	0.440		
	179.0	182.0	7159	3.0	0.590		
	182.0	183.1	7160	1.1	0.420		
	183.1	183.5	7161	0.4	4.520		
	183.5	186.5	7162	3.0	0.585		
	186.5	189.5	7164	3.0	0.745		
	189.5	192.5	7165	3.0	0.445		
	192.5	194.0	7166	1.5	0.745		
	194.0	195.5	7167	1.5	0.305	4.6	343
	195.5	196.6	7168	1.1	2.760	4.8	250
	196.6	197.4	7169	0.8	1.090	19.1	821
	197.4	199.3	7170	1.9	0.935	2.4	440
	199.3	201.0	7171	1.7	0.545	2.7	318
	201.0	202.5	7172	1.5	0.450	4.7	938
	202.5	205.5	7174	3.0	0.345		
	205.5	208.0	7175	2.5	0.345		
	208.0	209.6	7176	1.6	0.230	1.5	57
	209.6	210.0	7177	0.4	0.375	4.2	733
	210.0	210.6	7178	0.6	0.500	3.5	274
	210.6	210.8	7179	0.2	0.195	6.7	1309
	210.8	212.0	7180	1.2	0.225	2.0	157
	212.0	213.5	7181	1.5	0.260	2.2	131
	213.5	214.5	7182	1.0	0.490	1.4	196
	214.5	215.7	7184	1.2	1.080	3.3	215
	215.7	217.5	7185	1.8	1.090	2.1	263
	217.5	219.0	7186	1.5	1.500	1.6	480
	219.0	220.5	7187	1.5	0.390	3.3	505
	220.5	222.0	7188	1.5	0.225	3.1	185
	222.0	225.0	7189	3.0	0.360		
	225.0	228.0	7190	3.0	0.430		
	228.0	231.0	7191	3.0	0.280		
233.2m End of Hole	231.0	233.2	7192	2.2	0.165		

**Appendix 4**  
**Assays**





# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers  
 212 Brooksbank Ave., North Vancouver  
 British Columbia, Canada V7J 2C1  
 PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION  
 CATHEDRAL PLACE  
 910 - 925 W. GEORGIA ST.  
 VANCOUVER, BC  
 V6C 3L2

Page Number : 1  
 Total Pages : 1  
 Certificate Date: 09-AUG-97  
 Invoice No. : 19735737  
 P.O. Number :  
 Account : BQL

Project :  
 Comments: ATTN: DAVE YEAGER

## CERTIFICATE OF ANALYSIS A9735737

SAMPLE	PREP CODE	Au g/t FA+AA	Au FA g/t									
5349	205 226	0.315	-----									
5350	205 226	1.075	-----									
5351	205 226	0.610	-----									
5352	205 226	1.270	-----									
5353	205 226	0.010	-----									
5354	205 226	1.215	-----									
5355	205 226	3.68	-----									
5356	205 226	0.360	-----									
5357	205 226	0.285	-----									
5358	205 226	0.355	-----									
5359	205 226	0.360	-----									
5360	205 226	0.060	-----									
5361	205 226	0.080	-----									
5362	205 226	0.050	-----									
5363	205 226	< 0.005	-----									
5364	205 226	0.025	-----									
5365	205 226	0.160	-----									
5366	205 226	0.505	-----									
5367	205 226	0.070	-----									
5368	205 226	0.060	-----									
5369	205 226	0.075	-----									
5370	205 226	0.070	-----									
5371	205 226	0.080	-----									
5372	205 226	0.145	-----									
5373	205 226	< 0.005	-----									
5374	205 226	1.205	-----									
5375	205 226	>12.00	15.77									
5376	205 226	0.085	-----									
5377	205 226	0.125	-----									
5378	205 226	0.085	-----									

CERTIFICATION: \_\_\_\_\_



# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers

212 Brooksbank Ave., North Vancouver  
British Columbia, Canada V7J 2C1  
PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION  
CATHEDRAL PLACE  
910 - 925 W. GEORGIA ST.  
VANCOUVER, BC  
V6C 3L2

Page Number : 1  
Total Pages : 5  
Certificate Date: 14-AUG-97  
Invoice No. : 19734878  
P.O. Number :  
Account : BQL

Project : BRONSON SLOPE  
Comments : ATTN: DAVID YEAGER

## CERTIFICATE OF ANALYSIS A9734878

SAMPLE	PREP CODE	Au g/t FA+AA											
5001	205 226	0.050											
5002	205 226	0.150											
5003	205 226	0.005											
5004	205 226	0.240											
5005	205 226	0.170											
5006	205 226	0.115											
5007	205 226	0.035											
5008	205 226	0.065											
5009	205 226	0.035											
5010	205 226	0.050											
5011	205 226	0.095											
5012	205 226	0.170											
5013	205 226	< 0.005											
5014	205 226	0.075											
5015	205 226	0.020											
5016	205 226	0.035											
5017	205 226	0.080											
5018	205 226	0.070											
5019	205 226	0.110											
5020	205 226	0.100											
5021	205 226	0.135											
5022	205 226	0.240											
5023	205 226	< 0.005											
5024	205 226	0.095											
5025	205 226	0.130											
5026	205 226	0.065											
5027	205 226	0.160											
5028	205 226	0.095											
5029	205 226	0.060											
5030	205 226	0.060											
5031	205 226	0.115											
5032	205 226	0.150											
5033	205 226	< 0.005											
5034	205 226	0.420											
5035	205 226	0.170											
5036	205 226	0.090											
5037	205 226	0.030											
5038	205 226	0.080											
5039	205 226	0.060											
5040	205 226	0.035											

CERTIFICATION:

*David Yeager*



# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers  
212 Brooksbank Ave., North Vancouver  
British Columbia, Canada V7J 2C1  
PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION  
CATHEDRAL PLACE  
910 - 925 W. GEORGIA ST.  
VANCOUVER, BC  
V6C 3L2

Project: BRONSON SLOPE  
Comments: ATTN: DAVID YEAGER

Page Number :2  
Total Pages :5  
Certificate Date: 14-AUG-97  
Invoice No. :19734878  
P.O. Number :  
Account :BQL

## CERTIFICATE OF ANALYSIS A9734878

SAMPLE	PREP CODE	Au g/t FA+AA										
5041	205 226	0.145										
5042	205 226	0.500										
5043	205 226	0.010										
5044	205 226	0.160										
5045	205 226	0.590										
5046	205 226	3.44										
5047	205 226	0.435										
5048	205 226	1.735										
5049	205 226	0.590										
5050	205 226	0.275										
5051	205 226	0.090										
5052	205 226	0.235										
5053	205 226	< 0.005										
5054	205 226	0.180										
5055	205 226	0.145										
5056	205 226	0.250										
5057	205 226	0.095										
5058	205 226	0.090										
5059	205 226	0.065										
5060	205 226	0.085										
5061	205 226	0.030										
5062	205 226	0.010										
5063	205 226	< 0.005										
5064	205 226	0.125										
5065	205 226	0.660										
5066	205 226	0.250										
5067	205 226	0.095										
5068	205 226	0.050										
5069	205 226	0.060										
5070	205 226	0.040										
5071	205 226	0.170										
5072	205 226	0.205										
5073	205 226	< 0.005										
5074	205 226	0.180										
5075	205 226	0.235										
5076	205 226	0.250										
5077	205 226	0.285										
5078	205 226	0.075										
5079	205 226	0.220										
5080	205 226	0.180										

CERTIFICATION: David Yeager



# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers  
 212 Brooksbank Ave., North Vancouver  
 British Columbia, Canada V7J 2C1  
 PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION  
 CATHEDRAL PLACE  
 910 - 925 W. GEORGIA ST.  
 VANCOUVER, BC  
 V6C 3L2

Page Number : 3  
 Total Pages : 5  
 Certificate Date: 14-AUG-97  
 Invoice No. : 19734878  
 P.O. Number :  
 Account : BQL

Project : BRONSON SLOPE  
 Comments: ATTN: DAVID YEAGER

## CERTIFICATE OF ANALYSIS A9734878

SAMPLE	PREP CODE	Au g/t FA+AA										
5081	205 226	0.085										
5082	205 226	< 0.005										
5083	205 226	< 0.005										
5084	205 226	< 0.005										
5085	205 226	0.010										
5086	205 226	0.065										
5087	205 226	0.100										
5088	205 226	0.220										
5089	205 226	0.075										
5090	205 226	0.115										
5091	205 226	0.155										
5092	205 226	0.190										
5093	205 226	0.010										
5094	205 226	0.345										
5095	205 226	0.175										
5096	205 226	0.565										
5097	205 226	0.630										
5098	205 226	0.320										
5099	205 226	0.170										
5100	205 226	0.185										
5101	205 226	0.640										
5102	205 226	0.450										
5103	205 226	< 0.005										
5104	205 226	0.285										
5105	205 226	0.320										
5106	205 226	0.200										
5107	205 226	0.280										
5108	205 226	1.040										
5109	205 226	0.800										
5110	205 226	0.200										
5111	205 226	0.230										
5112	205 226	4.20										
5113	205 226	< 0.005										
5114	205 226	1.095										
5115	205 226	0.350										
5116	205 226	0.315										
5117	205 226	0.280										
5118	205 226	0.485										
5119	205 226	0.760										
5120	205 226	0.200										

CERTIFICATION: *David Yeager*



# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers

212 Brooksbank Ave., North Vancouver  
British Columbia, Canada V7J 2C1  
PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION  
CATHEDRAL PLACE  
910 - 925 W. GEORGIA ST.  
VANCOUVER, BC  
V6C 3L2

Project : BRONSON SLOPE  
Comments: ATTN: DAVID YEAGER

Page Number : 4  
Total Pages : 5  
Certificate Date: 14-AUG-97  
Invoice No. : 19734878  
P.O. Number :  
Account : BQL

## CERTIFICATE OF ANALYSIS

A9734878

SAMPLE	PREP CODE	Au g/t FA+AA																		
5121	205	226	0.370																	
5122	205	226	0.120																	
5123	205	226	0.015																	
5124	205	226	0.125																	
5125	205	226	0.705																	
5126	205	226	0.560																	
5127	205	226	0.410																	
5128	205	226	0.440																	
5129	205	226	0.420																	
5130	205	226	0.245																	
5131	205	226	0.170																	
5132	205	226	0.030																	
5133	205	226	0.020																	
5134	205	226	0.020																	
5135	205	226	0.160																	
5136	205	226	0.410																	
5137	205	226	1.560																	
5138	205	226	0.125																	
5139	205	226	0.075																	
5140	205	226	0.060																	
5141	205	226	0.075																	
5142	205	226	0.100																	
5143	205	226	0.035																	
5144	205	226	0.085																	
5145	205	226	0.130																	
5146	205	226	0.070																	
5147	205	226	0.115																	
5148	205	226	0.060																	
5149	205	226	0.160																	
5150	205	226	0.950																	
5151	205	226	0.100																	
5152	205	226	0.190																	
5153	205	226	0.010																	
5154	205	226	0.325																	
5155	205	226	0.400																	
5156	205	226	0.595																	
5157	205	226	0.475																	
5158	205	226	0.280																	
5159	205	226	0.250																	
5160	205	226	0.160																	

CERTIFICATION:

*David Yeager*



# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers  
212 Brooksbank Ave., North Vancouver  
British Columbia, Canada V7J 2C1  
PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION  
CATHEDRAL PLACE  
910 - 925 W. GEORGIA ST.  
VANCOUVER, BC  
V6C 3L2

Project: BRONSON SLOPE  
Comments: ATTN: DAVID YEAGER

Page Number :5  
Total Pages :5  
Certificate Date: 14-AUG-97  
Invoice No. : I9734878  
P.O. Number :  
Account : BQL

## CERTIFICATE OF ANALYSIS

A9734878

SAMPLE	PREP CODE	Au g/t FA+AA										
5161	205 226	0.210										
5162	205 226	1.150										
5163	205 226	0.015										
5164	205 226	1.260										
5165	205 226	0.230										
5166	205 226	0.900										
5167	205 226	0.295										
5168	205 226	0.185										
5169	205 226	0.095										
5170	205 226	0.665										
5171	205 226	0.705										
5172	205 226	2.88										
5173	205 226	0.010										
5174	205 226	0.220										
5175	205 226	0.205										
5176	205 226	0.380										

CERTIFICATION:

*Mark Work*



# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers  
 212 Brooksbank Ave., North Vancouver  
 British Columbia, Canada V7J 2C1  
 PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION  
 CATHEDRAL PLACE  
 910 - 925 W. GEORGIA ST.  
 VANCOUVER, BC  
 V6C 3L2

Project: BRONSON SLOPE  
 Comments: ATTN: DAVID YEAGER

Page Number : 1  
 Total Pages : 4  
 Certificate Date: 06-AUG-97  
 Invoice No. : 19735319  
 P.O. Number :  
 Account : BQL

## CERTIFICATE OF ANALYSIS

### A9735319

SAMPLE	PREP CODE	Au g/t FA+AA										
5177	205	226	0.170									
5178	205	226	0.315									
5179	205	226	1.155									
5180	205	226	0.185									
5181	205	226	0.100									
5182	205	226	0.210									
5183	205	226	0.015									
5184	205	226	0.435									
5185	205	226	1.800									
5186	205	226	0.340									
5187	205	226	0.370									
5188	205	226	0.325									
5189	205	226	0.185									
5190	205	226	0.335									
5191	205	226	0.195									
5192	205	226	0.140									
5193	205	226	0.015									
5194	205	226	0.120									
5195	205	226	0.520									
5196	205	226	0.245									
5197	205	226	0.750									
5198	205	226	0.180									
5199	205	226	1.920									
5200	205	226	0.305									
5201	205	226	0.070									
5202	205	226	0.065									
5203	205	226	0.015									
5204	205	226	0.040									
5205	205	226	0.140									
5206	205	226	0.380									
5207	205	226	0.195									
5208	205	226	0.205									
5209	205	226	0.200									
5210	205	226	1.185									
5211	205	226	2.29									
5212	205	226	0.465									
5213	205	226	0.015									
5214	205	226	0.500									
5215	205	226	0.145									
5216	205	226	0.650									

CERTIFICATION: *David Yeager*



# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers

212 Brooksbank Ave., North Vancouver  
British Columbia, Canada V7J 2C1  
PHONE: 604-984 0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION  
CATHEDRAL PLACE  
910 - 925 W. GEORGIA ST.  
VANCOUVER, BC  
V6C 3L2

Project: BRONSON SLOPE  
Comments: ATTN: DAVID YEAGER

Page Number : 2  
Total Pages : 4  
Certificate Date: 06-AUG-97  
Invoice No. : 19735319  
P.O. Number :  
Account : BQL

## CERTIFICATE OF ANALYSIS

A9735319

SAMPLE	PREP CODE		Au g/t FA+AA										
5217	205	226	0.260										
5218	205	226	0.150										
5219	205	226	0.130										
5220	205	226	0.180										
5221	205	226	0.070										
5222	205	226	0.070										
5223	205	226	0.010										
5224	205	226	0.110										
5225	205	226	0.075										
5226	205	226	0.140										
5227	205	226	0.030										
5228	205	226	0.090										
5229	205	226	0.100										
5230	205	226	0.065										
5231	205	226	0.090										
5232	205	226	0.045										
5233	205	226	< 0.005										
5234	205	226	0.050										
5235	205	226	0.070										
5236	205	226	0.035										
5237	205	226	0.055										
5238	205	226	0.035										
5239	205	226	0.025										
5240	205	226	0.110										
5241	205	226	0.025										
5242	205	226	0.060										
5243	205	226	< 0.005										
5244	205	226	0.030										
5245	205	226	0.025										
5246	205	226	0.020										
5247	205	226	0.035										
5248	205	226	0.025										
5249	205	226	0.035										
5250	205	226	0.120										
5251	205	226	0.040										
5252	205	226	0.055										
5253	205	226	< 0.005										
5254	205	226	0.015										
5255	205	226	0.020										
5256	205	226	0.030										

CERTIFICATION:

*David Yeager*





# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers  
 212 Brooksbank Ave., North Vancouver  
 British Columbia, Canada V7J 2G1  
 PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION  
 CATHEDRAL PLACE  
 910 - 925 W. GEORGIA ST.  
 VANCOUVER, BC  
 V6C 3L2

Page Number : 3  
 Total Pages : 4  
 Certificate Date: 06-AUG-97  
 Invoice No. : 19735319  
 P.O. Number :  
 Account : BQL

Project : BRONSON SLOPE  
 Comments: ATTN: DAVID YEAGER

## CERTIFICATE OF ANALYSIS A9735319

SAMPLE	PREP CODE	Au g/t FA+AA													
5257	205 226	0.040													
5258	205 226	0.020													
5259	205 226	0.015													
5260	205 226	0.010													
5261	205 226	0.015													
5262	205 226	0.030													
5263	205 226	< 0.005													
5264	205 226	0.050													
5265	205 226	0.035													
5266	205 226	0.030													
5267	205 226	0.065													
5268	205 226	< 0.005													
5269	-- --	Not Recd													
5270	-- --	Not Recd													
5271	-- --	Not Recd													
5272	-- --	Not Recd													
5273	-- --	Not Recd													
5274	205 226	0.195													
5275	205 226	0.160													
5276	205 226	0.180													
5277	205 226	0.080													
5278	205 226	0.125													
5279	205 226	0.425													
5280	205 226	0.110													
5281	205 226	0.055													
5282	205 226	< 0.005													
5283	205 226	0.040													
5284	205 226	0.095													
5285	205 226	0.040													
5286	205 226	0.025													
5287	205 226	0.025													
5288	205 226	0.020													
5289	205 226	0.025													
5290	205 226	0.030													
5291	205 226	0.030													
5292	205 226	0.020													
5293	205 226	< 0.005													
5294	205 226	0.020													
5295	205 226	0.015													
5296	205 226	0.015													

CERTIFICATION:

*David Yeager*



# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers  
 212 Brooksbank Ave., North Vancouver  
 British Columbia, Canada V7J 2C1  
 PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION  
 CATHEDRAL PLACE  
 910 - 925 W. GEORGIA ST.  
 VANCOUVER, BC  
 V6C 3L2

Page Number : 4  
 Total Pages : 4  
 Certificate Date: 06-AUG-97  
 Invoice No. : 19735319  
 P.O. Number :  
 Account : BQL

Project : BRONSON SLOPE  
 Comments : ATTN: DAVID YEAGER

## CERTIFICATE OF ANALYSIS A9735319

SAMPLE	PREP CODE	Au g/t FA+AA												
5297	205 226	0.025												
5298	205 226	0.030												
5299	205 226	0.130												
5300	205 226	0.040												
5301	205 226	0.080												
5302	205 226	0.120												
5303	205 226	< 0.005												
5304	205 226	0.025												
5305	205 226	0.035												
5306	205 226	0.070												
5307	205 226	0.240												
5308	205 226	0.045												
5309	205 226	0.060												
5310	205 226	0.050												
5311	205 226	0.060												
5312	205 226	0.090												
5313	205 226	0.050												
5314	205 226	0.110												
5315	205 226	0.080												
5316	205 226	0.065												
5317	205 226	0.320												
5318	205 226	0.090												
5319	205 226	0.020												
5320	205 226	0.020												
5321	205 226	0.010												
5322	205 226	0.080												
5323	205 226	< 0.005												
5324	205 226	0.040												
5325	205 226	0.030												
5326	205 226	0.040												
5327	205 226	0.025												
5328	205 226	0.030												
5329	205 226	0.045												
5330	205 226	0.040												
5331	205 226	0.025												
5332	205 226	0.050												
5333	205 226	0.025												
5334	205 226	0.040												
5335	205 226	0.065												

CERTIFICATION:

*David Yeager*



# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers  
 212 Brooksbank Ave., North Vancouver  
 British Columbia, Canada V7J 2C1  
 PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION \*\*  
 CATHEDRAL PLACE  
 910 - 925 W. GEORGIA ST.  
 VANCOUVER, BC  
 V6C 3L2

Page Number : 1  
 Total Pages : 5  
 Certificate Date: 30-JUL-97  
 Invoice No. : 19733221  
 P.O. Number :  
 Account : BQL

Project: BRONSON SLOPE  
 Comments: ATTN: DAVID YEAGER

## CERTIFICATE OF ANALYSIS A9733221

SAMPLE	PREP CODE		Au g/t FA+AA	Au FA g/t								
7029	205	226	0.010	-----								
7030	205	226	0.035	-----								
7031	205	226	0.010	-----								
7032	205	226	0.030	-----								
7033	205	226	< 0.005	-----								
7034	205	226	0.025	-----								
7035	205	226	0.035	-----								
7036	205	226	0.025	-----								
7037	205	226	0.030	-----								
7038	205	226	0.020	-----								
7039	205	226	0.060	-----								
7040	205	226	0.025	-----								
7041	205	226	0.030	-----								
7042	205	226	0.035	-----								
7043	205	226	0.005	-----								
7044	205	226	0.040	-----								
7045	205	226	0.050	-----								
7046	205	226	0.065	-----								
7047	205	226	0.055	-----								
7048	205	226	0.070	-----								
7049	205	226	0.040	-----								
7050	205	226	0.120	-----								
7051	205	226	0.150	-----								
7052	205	226	0.060	-----								
7053	205	226	0.010	-----								
7054	205	226	0.135	-----								
7055	205	226	2.58	-----								
7056	205	226	0.055	-----								
7057	205	226	0.025	-----								
7058	205	226	0.030	-----								
7059	205	226	0.050	-----								
7060	205	226	0.020	-----								
7061	205	226	0.010	-----								
7062	205	226	0.005	-----								
7063	205	226	0.020	-----								
7064	205	226	0.010	-----								
7065	205	226	0.050	-----								
7066	205	226	0.070	-----								
7067	205	226	0.515	-----								
7068	205	226	0.065	-----								

CERTIFICATION: *David Yeager*



# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers  
 212 Brooksbank Ave., North Vancouver  
 British Columbia, Canada V7J 2C1  
 PHONE: 604-984-0221 FAX: 604 984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION  
 CATHEDRAL PLACE  
 910 - 925 W. GEORGIA ST.  
 VANCOUVER, BC  
 V6C 3L2

Project: BRONSON SLOPE  
 Comments: ATTN: DAVID YEAGER

Page Number :2  
 Total Pages :5  
 Certificate Date: 30-JUL-97  
 Invoice No. : 19733221  
 P.O. Number :  
 Account : BQL

## CERTIFICATE OF ANALYSIS A9733221

SAMPLE	PREP CODE	Au g/t FA+AA	Au FA g/t										
7069	205 226	0.025	-----										
7070	205 226	0.075	-----										
7071	205 226	0.330	-----										
7072	205 226	0.170	-----										
7073	205 226	0.015	-----										
7074	205 226	0.070	-----										
7075	205 226	0.945	-----										
7076	205 226	0.125	-----										
7077	205 226	0.310	-----										
7078	205 226	1.330	-----										
7079	205 226	3.46	-----										
7080	205 226	>12.00	39.22										
7081	205 226	0.215	-----										
7082	205 226	0.495	-----										
7083	205 226	0.015	-----										
7084	205 226	0.105	-----										
7085	205 226	0.065	-----										
7086	205 226	0.025	-----										
7087	205 226	0.095	-----										
7088	205 226	0.110	-----										
7089	205 226	0.060	-----										
7090	205 226	0.040	-----										
7091	205 226	0.050	-----										
7092	205 226	0.430	-----										
7093	205 226	< 0.005	-----										
7094	205 226	0.075	-----										
7095	205 226	0.065	-----										
7096	205 226	0.035	-----										
7097	205 226	0.380	-----										
7098	205 226	0.055	-----										
7099	205 226	0.095	-----										
7100	205 226	0.180	-----										
7101	205 226	0.105	-----										
7102	205 226	0.205	-----										
7103	205 226	0.015	-----										
7104	205 226	0.160	-----										
7105	205 226	0.260	-----										
7106	205 226	0.300	-----										
7107	205 226	0.110	-----										
7108	205 226	0.650	-----										

CERTIFICATION: \_\_\_\_\_



# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers  
 212 Brooksbank Ave., North Vancouver  
 British Columbia, Canada V7J 2G1  
 PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION \*\*  
 CATHEDRAL PLACE  
 910 - 925 W. GEORGIA ST.  
 VANCOUVER, BC  
 V6C 3L2

Page Number :3  
 Total Pages :5  
 Certificate Date: 30-JUL-97  
 Invoice No. : I9733221  
 P.O. Number :  
 Account : BQL

Project : BRONSON SLOPE  
 Comments: ATTN: DAVID YEAGER

<b>CERTIFICATE OF ANALYSIS</b>	<b>A9733221</b>
--------------------------------	-----------------

SAMPLE	PREP CODE	Au g/t FA+AA	Au FA g/t								
7109	205 226	0.355	-----								
7110	205 226	0.525	-----								
7111	205 226	0.540	-----								
7112	205 226	0.235	-----								
7113	205 226	0.015	-----								
7114	205 226	0.150	-----								
7115	205 226	0.450	-----								
7116	205 226	0.185	-----								
7117	205 226	0.390	-----								
7118	205 226	0.430	-----								
7119	205 226	0.765	-----								
7120	205 226	0.150	-----								
7121	205 226	0.340	-----								
7122	205 226	0.710	-----								
7123	205 226	< 0.005	-----								
7124	205 226	1.115	-----								
7125	205 226	0.585	-----								
7126	205 226	0.655	-----								
7127	205 226	1.030	-----								
7128	205 226	0.155	-----								
7129	205 226	0.250	-----								
7130	205 226	0.240	-----								
7131	205 226	0.255	-----								
7132	205 226	0.335	-----								
7133	205 226	< 0.005	-----								
7134	205 226	0.400	-----								
7135	205 226	0.220	-----								
7136	205 226	0.190	-----								
7137	205 226	0.305	-----								
7138	205 226	0.680	-----								
7139	205 226	0.240	-----								
7140	205 226	0.205	-----								
7141	205 226	0.135	-----								
7142	205 226	0.260	-----								
7143	205 226	< 0.005	-----								
7144	205 226	0.120	-----								
7145	205 226	0.130	-----								
7146	205 226	0.280	-----								
7147	205 226	0.605	-----								
7148	205 226	0.300	-----								

CERTIFICATION: *David Yeager*



# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers  
 212 Brooksbank Ave., North Vancouver  
 British Columbia, Canada V7J 2C1  
 PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION  
 CATHEDRAL PLACE  
 910 - 925 W. GEORGIA ST.  
 VANCOUVER, BC  
 V6C 3L2

Page Number :4  
 Total Pages :5  
 Certificate Date: 30-JUL-97  
 Invoice No. :19733221  
 P.O. Number :  
 Account :BQL

Project : BRONSON SLOPE  
 Comments : ATTN: DAVID YEAGER

## CERTIFICATE OF ANALYSIS A9733221

SAMPLE	PREP CODE	Au g/t FA+AA	Au FA g/t									
7149	205 226	0.490	-----									
7150	205 226	2.32	-----									
7151	205 226	0.425	-----									
7152	205 226	0.270	-----									
7153	205 226	< 0.005	-----									
7154	205 226	0.255	-----									
7155	205 226	0.535	-----									
7156	205 226	0.575	-----									
7157	205 226	0.815	-----									
7158	205 226	0.440	-----									
7159	205 226	0.590	-----									
7160	205 226	0.420	-----									
7161	205 226	4.52	-----									
7162	205 226	0.585	-----									
7163	205 226	< 0.005	-----									
7164	205 226	0.745	-----									
7165	205 226	0.445	-----									
7166	205 226	0.745	-----									
7167	205 226	0.305	-----									
7168	205 226	2.76	-----									
7169	205 226	1.090	-----									
7170	205 226	0.935	-----									
7171	205 226	0.545	-----									
7172	205 226	0.450	-----									
7173	205 226	< 0.005	-----									
7174	205 226	0.345	-----									
7175	205 226	0.345	-----									
7176	205 226	0.230	-----									
7177	205 226	0.375	-----									
7178	205 226	0.500	-----									
7179	205 226	0.195	-----									
7180	205 226	0.225	-----									
7181	205 226	0.260	-----									
7182	205 226	0.490	-----									
7183	205 226	< 0.005	-----									
7184	205 226	1.080	-----									
7185	205 226	1.090	-----									
7186	205 226	1.500	-----									
7187	205 226	0.390	-----									
7188	205 226	0.225	-----									

CERTIFICATION: *David Yeager*



# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers

212 Brooksbank Ave., North Vancouver  
British Columbia, Canada V7J 2C1  
PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION  
CATHEDRAL PLACE  
910 - 925 W. GEORGIA ST.  
VANCOUVER, BC  
V6C 3L2

Project : BRONSON SLOPE  
Comments: ATTN: DAVID YEAGER

Page Number :5  
Total Pages :5  
Certificate Date: 30-JUL-97  
Invoice No. : 19733221  
P.O. Number :  
Account : BQL

## CERTIFICATE OF ANALYSIS A9733221

SAMPLE	PREP CODE		Au g/t FA+AA	Au FA g/t								
7189	205	226	0.360	-----								
7190	205	226	0.430	-----								
7191	205	226	0.280	-----								
7192	205	226	0.165	-----								

CERTIFICATION: *David Yeager*



# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers  
 212 Brooksbank Ave., North Vancouver  
 British Columbia, Canada V7J 2C1  
 PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION  
 CATHEDRAL PLACE  
 910 - 925 W. GEORGIA ST.  
 VANCOUVER, BC  
 V6C 3L2

Page Number : 1  
 Total Pages : 4  
 Certificate Date: 29-JUL-97  
 Invoice No. : 19733384  
 P.O. Number :  
 Account : BQL

Project :  
 Comments: ATTN: DAVE YEAGER

## CERTIFICATE OF ANALYSIS A9733384

SAMPLE	PREP CODE		Au g/t FA+AA									
7193	205	226	0.015									
7194	205	226	0.010									
7195	205	226	0.120									
7196	205	226	0.015									
7197	205	226	0.005									
7198	205	226	0.020									
7199	205	226	0.015									
7200	205	226	0.025									
7201	205	226	0.020									
7202	205	226	0.015									
7203	205	226	< 0.005									
7204	205	226	0.020									
7205	205	226	0.040									
7206	205	226	0.030									
7207	205	226	0.045									
7208	205	226	0.055									
7209	205	226	0.050									
7210	205	226	0.065									
7211	205	226	0.035									
7212	205	226	0.010									
7213	205	226	< 0.005									
7214	205	226	0.175									
7215	205	226	0.020									
7216	205	226	0.075									
7217	205	226	0.045									
7218	205	226	0.140									
7219	205	226	0.100									
7220	205	226	0.225									
7221	205	226	2.74									
7222	205	226	2.34									
7223	205	226	0.010									
7224	205	226	0.110									
7225	205	226	0.045									
7226	205	226	0.310									
7227	205	226	0.060									
7228	205	226	0.035									
7229	205	226	0.025									
7230	205	226	0.020									
7231	205	226	0.010									
7232	205	226	0.030									

CERTIFICATION:

*David Voth*





# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers  
 212 Brooksbank Ave., North Vancouver  
 British Columbia, Canada V7J 2C1  
 PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION \*\*  
 CATHEDRAL PLAGE  
 910 - 925 W. GEORGIA ST.  
 VANCOUVER, BC  
 V6C 3L2

Page Number :2  
 Total Pages :4  
 Certificate Date: 29-JUL-97  
 Invoice No. :19733384  
 P.O. Number :  
 Account :BQL

Project :  
 Comments: ATTN: DAVE YEAGER

<b>CERTIFICATE OF ANALYSIS</b>	<b>A9733384</b>
--------------------------------	-----------------

SAMPLE	PREP CODE	Au g/t FA+AA								
7233	205 226	< 0.005								
7234	205 226	0.150								
7235	205 226	0.035								
7236	205 226	0.030								
7237	205 226	0.050								
7238	205 226	0.050								
7239	205 226	0.065								
7240	205 226	0.580								
7241	205 226	0.710								
7242	205 226	0.330								
7243	205 226	0.005								
7244	205 226	0.050								
7245	205 226	0.115								
7246	205 226	0.290								
7247	205 226	0.110								
7248	205 226	0.460								
7249	205 226	0.175								
7250	205 226	0.555								
7251	205 226	0.265								
7252	205 226	0.525								
7253	205 226	< 0.005								
7254	205 226	0.195								
7255	205 226	0.155								
7256	205 226	0.205								
7257	205 226	0.310								
7258	205 226	0.530								
7259	205 226	0.240								
7260	205 226	0.210								
7261	205 226	0.480								
7262	205 226	0.265								
7263	205 226	< 0.005								
7264	205 226	0.210								
7265	205 226	0.345								
7266	205 226	0.085								
7267	205 226	0.205								
7268	205 226	0.080								
7269	205 226	0.090								
7270	205 226	0.070								
7271	205 226	0.070								
7272	205 226	0.190								

CERTIFICATION: \_\_\_\_\_



# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers

212 Brooksbank Ave., North Vancouver  
British Columbia, Canada V7J 2G1  
PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION  
CATHEDRAL PLACE  
910 - 925 W. GEORGIA ST.  
VANCOUVER, BC  
V6C 3L2

Page Number :3  
Total Pages :4  
Certificate Date: 29-JUL-97  
Invoice No. :19733384  
P.O. Number :  
Account :BQL

Project :  
Comments: ATTN: DAVE YEAGER

## CERTIFICATE OF ANALYSIS

A9733384

SAMPLE	PREP CODE	Au g/t FA+AA											
7273	205	226	< 0.005										
7274	205	226	0.140										
7275	205	226	0.140										
7276	205	226	0.200										
7277	205	226	0.170										
7278	205	226	0.135										
7279	205	226	0.190										
7280	205	226	0.020										
7281	205	226	0.045										
7282	205	226	0.010										
7283	205	226	< 0.005										
7284	205	226	0.050										
7285	205	226	0.305										
7286	205	226	0.260										
7287	205	226	0.100										
7288	205	226	0.080										
7289	205	226	0.350										
7290	205	226	0.200										
7291	205	226	0.090										
7292	205	226	0.195										
7293	205	226	< 0.005										
7294	205	226	0.225										
7295	205	226	0.270										
7296	205	226	0.170										
7297	205	226	0.660										
7298	205	226	0.425										
7299	205	226	0.265										
7300	205	226	0.580										
7301	205	226	0.865										
7302	205	226	0.430										
7303	205	226	< 0.005										
7304	205	226	0.185										
7305	205	226	1.660										
7306	205	226	1.030										
7307	205	226	0.735										
7308	205	226	0.270										
7309	205	226	0.520										
7310	205	226	0.610										
7311	205	226	0.680										
7312	205	226	0.450										

CERTIFICATION:

*Mark Vonk*



# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers  
212 Brooksbank Ave., North Vancouver  
British Columbia, Canada V7J 2C1  
PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION  
CATHEDRAL PLACE  
910 - 925 W. GEORGIA ST.  
VANCOUVER, BC  
V6C 3L2

Page Number :4  
Total Pages :4  
Certificate Date: 29-JUL-97  
Invoice No. : 19733384  
P.O. Number :  
Account : BQL

Project :  
Comments: ATIN: DAVE YEAGER

## CERTIFICATE OF ANALYSIS A9733384

SAMPLE	PREP CODE	Au g/t FA+AA										
7313	205	226	< 0.005									
7314	205	226	0.520									
7315	205	226	0.900									
7316	205	226	0.270									
7317	205	226	0.250									
7318	205	226	0.260									
7319	205	226	0.280									
7320	205	226	0.120									
7321	205	226	0.340									
7322	205	226	0.200									
7323	205	226	0.010									
7324	205	226	0.260									
7325	205	226	0.180									
7326	205	226	0.230									
7327	205	226	0.150									
7328	205	226	0.155									
7329	205	226	0.090									
7330	205	226	0.160									
7331	205	226	4.92									
7332	205	226	0.800									
7333	205	226	0.020									
7334	205	226	1.000									
7335	205	226	0.460									
7336	205	226	0.170									
7337	205	226	5.16									
7338	205	226	0.485									
7339	205	226	0.890									
7340	205	226	0.360									
7341	205	226	0.590									

CERTIFICATION: *Theresa Vank*



# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers

212 Brooksbank Ave., North Vancouver  
British Columbia, Canada V7J 2C1  
PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION \*\*  
CATHEDRAL PLACE  
910 - 925 W. GEORGIA ST.  
VANCOUVER, BC  
V6C 3L2

Page Number : 1  
Total Pages : 3  
Certificate Date: 29-JUL-97  
Invoice No. : 19733751  
P.O. Number :  
Account : BQL

Project :  
Comments: ATTN: DAVE YEAGER

## CERTIFICATE OF ANALYSIS A9733751

SAMPLE	PREP CODE	Au g/t FA+AA										
7342	205 226	0.800										
7343	205 226	0.030										
7344	205 226	0.080										
7345	205 226	0.120										
7346	205 226	0.305										
7347	205 226	0.440										
7348	205 226	0.450										
7349	205 226	0.390										
7350	205 226	0.360										
7351	205 226	0.360										
7352	205 226	0.325										
7353	205 226	< 0.005										
7354	205 226	0.500										
7355	205 226	0.230										
7356	205 226	0.480										
7357	205 226	0.895										
7358	205 226	0.370										
7359	205 226	0.460										
7360	205 226	0.955										
7361	205 226	1.320										
7362	205 226	0.220										
7363	205 226	0.015										
7364	205 226	0.420										
7365	205 226	0.590										
7366	205 226	0.180										
7367	205 226	0.170										
7368	205 226	0.095										
7369	205 226	1.515										
7370	205 226	0.375										
7371	205 226	0.775										
7372	205 226	0.100										
7373	205 226	0.005										
7374	205 226	0.100										
7375	205 226	1.400										
7376	205 226	0.080										
7377	205 226	0.655										
7378	205 226	0.185										
7379	205 226	2.25										
7380	205 226	0.200										
7381	205 226	2.01										

CERTIFICATION:

*David Vank*



# Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers  
 212 Brooksbank Ave., North Vancouver  
 British Columbia, Canada V7J 2C1  
 PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION  
 CATHEDRAL PLACE  
 910 - 925 W. GEORGIA ST.  
 VANCOUVER, BC  
 V6C 3L2

Page Number : 2  
 Total Pages : 3  
 Certificate Date: 29-JUL-97  
 Invoice No. : 19733751  
 P.O. Number :  
 Account : BQL

Project:  
 Comments: ATIN: DAVE YEAGER

## CERTIFICATE OF ANALYSIS

A9733751

SAMPLE	PREP CODE	AU g/t FA+AA																	
7382	205 226	0.045																	
7383	205 226	0.015																	
7384	205 226	0.050																	
7385	205 226	0.080																	
7386	205 226	0.095																	
7387	205 226	0.210																	
7388	205 226	0.060																	
7389	205 226	0.085																	
7390	205 226	0.100																	
7391	205 226	0.155																	
7392	205 226	0.130																	
7393	205 226	0.015																	
7394	205 226	0.145																	
7395	205 226	0.070																	
7396	205 226	0.250																	
7397	205 226	0.110																	
7398	205 226	0.065																	
7399	205 226	0.040																	
7400	205 226	0.150																	
7401	205 226	0.290																	
7402	205 226	0.230																	
7403	205 226	0.010																	
7404	205 226	0.270																	
7405	205 226	0.430																	
7406	205 226	0.130																	
7407	205 226	0.075																	
7408	205 226	0.070																	
7409	205 226	0.090																	
7410	205 226	0.170																	
7411	205 226	0.125																	
7412	205 226	0.140																	
7413	205 226	0.010																	
7414	205 226	0.105																	
7415	205 226	0.325																	
7416	205 226	0.405																	
7417	205 226	0.165																	
7418	205 226	0.110																	
7419	205 226	0.120																	
7420	205 226	0.060																	
7421	205 226	0.045																	

CERTIFICATION: *Frank Vonk*



# Chemex Labs Ltd.

Analytical Chemists \* Geochemists \* Registered Assayers  
212 Brooksbank Ave., North Vancouver  
British Columbia, Canada V7J 2C1  
PHONE: 604-984-0221 FAX: 604-984-0218

To: INTERNATIONAL SKYLINE GOLD CORPORATION  
CATHEDRAL PLACE  
910 - 925 W. GEORGIA ST.  
VANCOUVER, BC  
V6C 3L2

Project:   
Comments: ATTN: DAVE YEAGER

Page Number : 3  
Total Pages : 3  
Certificate Date: 29-JUL-97  
Invoice No. : 19733751  
P.O. Number :  
Account : BQL

## CERTIFICATE OF ANALYSIS A9733751

SAMPLE	PREP CODE	Au g/t FA+AA																				
7422	205 226	0.050																				
7423	205 226	0.015																				
7424	205 226	0.080																				
7425	205 226	0.115																				
7426	205 226	0.135																				
7427	205 226	0.140																				
7428	205 226	0.145																				
7429	205 226	0.130																				
7430	205 226	0.110																				
7431	205 226	0.070																				
7432	205 226	0.125																				
7433	205 226	0.010																				
7434	205 226	0.365																				
7435	205 226	0.210																				
7436	205 226	0.060																				
7437	205 226	0.055																				
7438	205 226	2.21																				
7439	205 226	0.070																				
7440	205 226	0.160																				
7441	205 226	0.140																				
7442	205 226	0.455																				
7443	205 226	0.010																				
7444	205 226	0.125																				
7445	205 226	0.170																				
7446	205 226	1.270																				
7447	205 226	0.275																				
7448	205 226	0.115																				
7449	205 226	0.080																				
7450	205 226	0.110																				
7451	205 226	0.120																				
7452	205 226	0.270																				
7453	205 226	0.020																				
7454	205 226	0.210																				
7455	205 226	0.075																				

CERTIFICATION: *David Viner*