

RECEIVED
JAN 19 1998
Gold Commissioner's Office
VANCOUVER, B.C.

APPENDIX I

**Geochemical Analysis and Assay Results for the
Trenching, Geochemical and Drill Program**

**GEOLOGICAL SURVEY BRANCH
ASSESSMENT REPORT**

25,335

GEOCHEMICAL ANALYSIS CERTIFICATE

TEUTON RESOURCES CORP.

Project:

Sample Type: Rocks

Multi-element ICP Analysis - .500 gram sample is digested with 3 ml of aqua regia, diluted to 10 ml with Water. This leach is partial for Mn, Fe, Ca, P, La, Cr, Mg, Ba, Ti, B, W and limited for Na, K and Al. Detection Limit for Au is 3 ppm.
 *Au Analysis- 10 gram sample is digested with aqua regia, NIBK extracted, graphite furnace AA finished to 1 ppb detection.

Analyst R Sam
 Report No. 9722287
 Date: September 15, 1997

ELEMENT SAMPLE	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Be ppm	Ti %	B %	Al %	Na %	K %	W ppm	Al ^h ppb
✓ C 5+50E 25+00N	2	27	14	80	.3	4	10	770	3.97	2	8	ND	4	50	.7	3	3	81	1.03	.102	10	38	.92	126	.16	8	1.41	.08	.13	2	2
✓ C 5+50E 25+25N	2	12	12	106	.3	3	16	1058	3.58	4	8	ND	4	104	.8	3	3	76	1.05	.109	11	33	1.71	171	.22	5	2.30	.05	.12	2	1
✓ C 5+50E 26+00N	1	11	14	71	.3	7	7	730	3.91	2	8	ND	3	66	.7	3	3	100	2.17	.105	10	39	.91	112	.16	4	1.37	.14	.14	2	1
✓ C 5+50E 30+00N	1	8	10	144	.3	8	18	1001	4.99	2	8	ND	2	91	.6	3	3	105	1.19	.118	8	23	1.58	99	.20	8	2.20	.08	.18	2	1
C 6+00E 21+50N	1	6	4	49	.3	6	14	902	3.77	2	8	ND	3	41	.2	3	3	77	.63	.109	10	25	.98	86	.16	4	1.58	.04	.22	2	1
C 6+50E 21+50N	1	25	3	89	.3	4	14	1120	4.42	2	8	ND	3	51	.2	3	3	109	1.47	.112	9	26	1.50	77	.17	5	1.95	.09	.12	2	7
C 6+50E 22+00N	1	2	3	87	.3	6	21	956	4.28	5	8	ND	2	133	.2	3	3	70	1.17	.119	4	27	1.68	32	.16	3	2.32	.04	.06	2	12
C 6+50E 22+25N	1	2	9	140	.3	7	31	971	6.39	2	8	ND	2	104	.2	3	3	204	1.50	.104	4	20	1.79	228	.23	3	2.58	.34	.14	2	17
C 6+50E 22+50N	1	1	10	77	.3	6	18	975	5.40	2	8	ND	2	85	.2	3	3	144	1.31	.104	4	8	1.24	86	.17	3	2.25	.23	.11	2	1
C 6+50E 22+75N	1	9	3	119	.3	5	24	1375	5.99	5	8	ND	2	87	.2	3	3	138	.85	.106	4	5	1.98	97	.25	3	2.22	.08	.09	2	25
C 6+50E 23+00N	1	4	3	103	.3	3	19	1207	6.00	2	8	ND	2	115	.2	3	3	143	1.61	.100	4	10	1.53	110	.25	3	2.77	.35	.14	2	1
C 6+50E 23+50N	1	69	3	86	.3	1	15	1130	4.92	2	8	ND	3	46	.2	3	3	78	1.55	.113	9	10	1.40	206	.19	3	2.12	.07	.29	17	1
C 6+50E 23+75N	1	5	14	96	.3	3	16	1255	5.35	2	8	ND	2	42	.2	3	3	84	1.15	.116	9	10	1.58	270	.19	5	2.21	.07	.29	2	31
C 6+50E 24+00N	1	1	6	83	.3	1	15	1265	4.61	2	8	ND	2	68	.2	3	3	107	.92	.095	5	10	2.22	128	.19	3	2.67	.13	.13	2	7
C 6+50E 24+50N	1	2	6	66	.3	4	13	707	4.72	3	8	ND	2	131	.2	3	3	108	1.49	.131	6	9	1.10	96	.20	3	2.59	.34	.16	2	10
C 6+50E 24+75N	1	24	3	45	.3	4	14	806	3.93	2	8	ND	2	108	.3	3	3	86	2.10	.114	6	29	1.15	85	.15	3	1.67	.10	.12	2	3
C 6+50E 25+00N	1	2	3	57	.3	9	18	822	5.83	2	8	ND	2	26	.2	3	3	106	1.98	.132	3	13	1.38	261	.06	3	1.98	.03	.29	2	7
C 6+50E 25+25N	1	26	6	76	.3	2	14	1138	5.46	5	8	ND	2	85	.2	3	3	138	2.91	.126	7	16	1.32	229	.16	6	1.98	.19	.09	2	1
C 6+50E 25+50N	1	90	3	79	.3	11	19	958	4.95	2	8	ND	2	89	.2	3	3	137	1.86	.139	8	26	1.49	73	.21	3	2.28	.24	.12	2	1
C 6+50E 25+75N	2	117	6	105	.3	83	19	1246	4.62	2	8	ND	2	49	.3	3	3	111	1.87	.122	5	116	1.88	70	.19	3	2.28	.13	.11	2	3
C 6+50E 26+00N	1	85	7	53	.3	5	16	750	4.73	2	8	ND	2	99	.2	3	3	125	1.16	.149	6	22	.82	62	.18	3	1.79	.14	.15	2	10
C 6+50E 26+25N	1	1	5	101	.3	2	17	1168	4.16	2	8	ND	2	55	.2	3	3	104	.99	.083	5	20	1.92	143	.23	9	2.13	.13	.18	2	1
C 6+50E 26+50N	1	72	3	106	.3	7	20	1249	6.18	2	8	ND	2	77	.3	3	3	179	1.30	.107	5	12	2.08	101	.24	3	2.81	.19	.12	2	14
C 6+50E 26+75N	1	1	3	75	.3	4	15	850	5.02	2	8	ND	2	92	.2	3	3	112	1.06	.119	7	17	.95	109	.18	3	1.86	.18	.14	2	12
C 6+50E 27+00N	1	6	5	95	.3	3	13	1200	5.18	2	8	ND	2	71	.2	3	3	92	1.21	.133	5	16	.98	109	.15	5	2.00	.20	.16	2	6
C 6+50E 27+25N	1	4	5	57	.3	3	12	940	4.78	2	8	ND	2	81	.2	3	3	95	1.36	.124	4	9	1.09	98	.14	6	2.28	.28	.17	2	23
C 6+50E 27+50N	1	10	3	59	.3	3	17	804	5.73	3	8	ND	2	72	.2	3	3	167	1.04	.169	8	8	.79	116	.18	4	1.59	.14	.21	2	14
C 6+50E 27+75N	1	4	4	87	.3	2	16	1151	5.10	2	8	ND	2	106	.5	3	3	118	2.38	.156	8	9	1.05	238	.18	6	1.92	.20	.24	2	28
C 6+50E 28+25N	1	42	4	105	.3	4	17	1301	4.20	2	8	ND	3	83	.2	3	3	95	1.04	.125	9	13	1.58	82	.22	5	2.34	.11	.11	2	11
C 6+50E 28+50N	1	12	3	70	.3	5	16	1178	5.54	2	8	ND	3	61	.3	3	3	103	1.95	.136	9	9	1.31	130	.20	3	2.32	.18	.26	2	17

ELEMENT SAMPLE	Mn	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Hg	Ba	Tl	B	Al	Na	K	W	Au
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm
C 6+50E 28+75N	1	1	5	88	.3	4	24	851	6.68	2	8	ND	2	55	.2	3	3	198	.99	.113	6	7	1.86	117	.21	3	2.44	.14	.16	2	18
C 6+50E 29+00N	1	1	3	116	.3	5	27	847	4.25	2	8	ND	2	114	.3	3	3	152	2.43	.123	3	14	1.54	113	.19	3	2.56	.39	.12	2	4
C 6+50E 29+50N	1	1	3	56	.3	2	13	760	3.30	2	8	ND	2	66	.2	3	3	92	1.09	.108	5	20	1.32	90	.19	3	1.88	.23	.14	2	4
C 6+50E 29+75N	1	1	3	66	.3	5	16	706	5.20	2	8	ND	2	64	.2	3	3	175	1.30	.116	9	8	.94	129	.19	3	1.74	.21	.18	2	19
C 7+50E 21+50N	1	6	3	30	.3	3	8	636	4.02	3	8	ND	2	84	.2	3	3	65	1.20	.138	4	20	.60	115	.12	3	1.32	.09	.16	2	28
C 7+50E 21+75N	1	159	3	73	.6	21	16	951	5.31	2	8	ND	2	70	.2	3	3	108	.98	.115	6	32	1.35	91	.18	5	2.01	.14	.12	2	31
C 7+50E 22+00N	1	15	3	49	.3	7	10	709	4.05	2	8	ND	2	79	.2	3	3	115	1.03	.133	8	26	1.04	129	.20	4	1.74	.14	.18	2	2
C 7+50E 22+50N	1	27	4	64	.3	10	14	962	4.49	2	8	ND	2	74	.3	3	3	107	1.26	.126	6	30	1.18	62	.18	3	1.91	.13	.13	2	1
C 7+50E 23+00N	1	39	3	60	.3	5	13	692	3.89	2	8	ND	2	73	.2	3	3	111	1.06	.099	6	26	1.05	67	.21	3	1.82	.14	.12	2	3
C 7+50E 23+25N	1	87	3	63	.3	6	12	646	4.36	2	8	ND	2	86	.2	3	3	126	1.56	.135	6	11	.91	72	.18	3	1.84	.14	.14	2	7
C 7+50E 23+50N	1	8	3	104	.3	7	22	1138	4.85	4	8	ND	2	84	.4	3	3	108	1.30	.149	3	7	2.22	45	.16	3	2.56	.10	.08	2	17
C 7+50E 23+75N	1	7	6	31	.3	5	10	896	3.92	5	8	ND	3	38	.2	3	3	56	2.23	.114	8	6	1.08	120	.03	7	2.04	.04	.31	2	4
C 7+50E 24+00N	1	7	3	82	.3	6	12	1096	5.31	2	8	ND	3	35	.2	3	3	152	.60	.109	10	14	1.48	67	.19	3	2.72	.09	.12	2	12
C 7+50E 24+50N	1	3	3	75	.3	6	15	1330	6.04	2	8	ND	2	26	.2	3	3	106	.88	.126	3	7	2.13	137	.15	3	3.16	.05	.33	5	11
C 7+50E 24+75N	1	19	3	70	.3	17	12	762	3.66	3	8	ND	2	72	.2	3	3	101	1.25	.113	6	34	1.11	67	.27	3	2.31	.20	.11	2	8
C 7+50E 25+00N	1	3	3	67	.3	5	10	915	4.49	2	8	ND	2	84	.2	3	3	117	1.52	.143	5	4	.94	176	.14	5	1.97	.21	.20	2	19
C 7+50E 25+25N	1	16	6	94	.3	3	12	1159	4.23	2	8	ND	2	60	.2	3	3	105	1.03	.108	8	14	1.89	73	.26	3	2.67	.15	.11	2	4
C 7+50E 25+50N	1	3	3	50	.3	4	10	938	4.32	2	8	ND	3	144	.2	3	4	89	2.79	.123	9	14	1.00	292	.09	5	2.39	.28	.27	2	7
C 7+50E 25+75N	1	127	3	105	.5	12	17	1046	4.79	2	8	ND	2	60	.2	3	3	164	.91	.128	7	26	1.71	58	.22	3	2.19	.08	.87	2	34
C 7+50E 26+00N	1	80	3	80	.3	10	18	1376	5.48	2	8	ND	2	41	.2	3	3	160	2.00	.104	5	22	1.82	91	.20	3	2.49	.12	.18	2	15
C 7+50E 26+25N	1	2	3	55	.3	5	16	485	5.31	2	8	ND	2	69	.2	3	3	175	.95	.111	4	16	.78	83	.21	5	1.51	.12	.11	2	17
C 7+50E 26+50N	1	18	14	72	.3	77	10	162	3.18	12	8	ND	2	14	.2	3	3	36	.12	.053	2	84	.84	111	.02	5	1.61	.03	.18	2	4
C 7+50E 26+75N	2	38	7	91	.3	4	10	782	3.94	6	8	ND	6	46	.2	3	6	111	.69	.092	12	19	1.24	115	.20	3	2.14	.14	.13	2	7
C 7+50E 27+00N	1	7	3	44	.3	8	16	996	7.84	37	8	ND	2	10	.2	3	3	114	.39	.102	4	19	1.28	106	.10	8	2.83	.03	.33	8	70
C 7+50E 27+25N	1	5	3	40	.3	1	9	441	4.40	2	8	ND	2	74	.2	3	3	106	.99	.117	8	27	.75	61	.16	6	1.62	.10	.12	2	8
C 7+50E 27+50N	1	43	4	40	.3	2	17	594	4.39	2	8	ND	2	67	.2	3	4	121	.98	.110	8	22	.80	84	.18	5	1.83	.20	.13	2	19
C 7+50E 27+75N	1	52	3	47	.3	9	10	598	3.23	2	8	ND	2	55	.2	3	3	87	.94	.111	10	23	.78	130	.16	3	1.67	.09	.11	2	15
C 7+50E 28+00N	1	152	3	61	.4	11	9	695	3.30	2	8	ND	2	58	.2	3	5	88	.96	.121	8	22	.98	59	.15	3	1.73	.08	.09	2	8
C 7+50E 28+25N	1	11	7	91	.3	2	8	707	3.81	2	8	ND	3	60	.2	3	3	78	.77	.102	7	24	1.18	89	.15	3	2.19	.15	.12	2	12
C 7+50E 28+50N	1	122	3	61	.4	6	22	1010	4.28	4	8	ND	2	69	.2	3	3	79	1.08	.120	6	22	1.41	77	.12	3	2.03	.08	.12	2	11
C 7+50E 28+75N	1	147	5	82	.3	30	30	1411	7.20	2	8	ND	2	47	.2	3	3	300	1.46	.147	4	29	3.22	59	.17	7	3.14	.06	.09	2	20
C 7+50E 29+00N	1	27	5	50	.3	3	9	614	4.88	2	8	ND	2	70	.2	3	3	194	1.11	.118	8	14	.90	125	.16	4	1.84	.17	.18	2	9
C 7+50E 29+25N	1	47	3	37	.3	6	11	381	3.60	2	8	ND	2	79	.2	3	3	174	1.18	.121	9	28	.42	91	.17	3	1.52	.16	.16	2	18
C 7+50E 29+50N	1	8	3	67	.3	9	15	917	4.75	2	8	ND	2	22	1.0	3	3	137	.60	.111	9	9	1.26	123	.13	4	1.86	.06	.27	2	25
C 7+50E 29+75N	1	3	3	69	.3	8	16	1106	4.58	2	8	ND	2	49	.2	3	3	101	1.12	.112	9	18	1.64	124	.15	6	2.19	.09	.18	2	15

ELEMENT SAMPLE	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Me %	K %	M ppm	Au ppb
C 7+50E 30+00N	1	2	3	42	.3	7	12	832	4.10	2	8	ND	2	110	.2	3	3	143	1.58	.108	6	9	1.39	116	.14	3	2.37	.26	.14	4	17
C 8+50E 22+25N	1	11	3	104	.3	10	31	1100	6.69	3	8	ND	2	47	.2	3	3	171	.67	.113	4	14	2.14	69	.19	5	2.77	.07	.07	2	9
C 8+50E 22+50N	2	25	14	121	.7	35	19	1063	4.32	24	8	ND	2	47	.5	3	3	84	.79	.175	6	26	1.67	171	.09	4	2.21	.07	.18	2	17
C 8+50E 22+75N	1	1	3	85	.3	2	16	1038	4.90	2	8	ND	2	39	.2	3	5	97	1.54	.128	4	5	1.46	82	.12	3	1.97	.08	.12	2	23
C 8+50E 23+00N	1	2	4	112	.3	3	15	905	4.51	2	8	ND	2	87	.2	3	3	89	1.15	.115	4	10	1.17	88	.14	3	2.17	.22	.10	2	11
C 8+50E 23+50N	2	23	3	48	.3	7	24	719	5.26	2	8	ND	2	184	.5	3	3	131	2.47	.124	6	37	1.44	154	.19	3	3.65	.62	.18	2	5
C 8+50E 23+75N	1	10	6	70	.3	3	17	1040	6.18	2	8	ND	2	68	.2	3	3	107	.91	.119	4	9	1.79	93	.18	3	2.40	.12	.09	2	1
C 8+50E 24+00N	2	1	7	32	.3	7	6	403	3.24	2	8	ND	2	242	.3	3	6	102	1.70	.133	4	55	.64	46	.13	3	1.71	.10	.05	2	7
C 8+50E 24+25N	1	112	3	37	.3	6	15	511	3.65	5	8	ND	2	94	.2	3	3	128	1.35	.132	7	17	.69	67	.17	3	1.82	.20	.12	2	1
C 8+50E 24+50N	2	8	5	51	.3	4	10	967	3.90	2	8	ND	5	49	.2	3	3	103	1.00	.105	11	39	1.21	91	.18	3	1.81	.09	.14	2	6
C 8+50E 24+75N	1	13	3	101	.3	3	11	1656	5.78	17	8	ND	2	91	.2	3	4	160	2.01	.110	10	19	2.31	111	.22	3	3.40	.34	.08	2	19
C 8+50E 25+00N	1	60	3	82	.3	23	13	1137	5.77	2	8	ND	3	114	.2	3	3	131	1.28	.110	8	42	1.77	142	.23	3	3.02	.31	.14	2	20
C 8+50E 25+25N	2	130	7	85	.3	9	24	933	7.59	2	8	ND	2	35	.5	3	3	204	.71	.095	4	43	1.23	112	.36	3	1.97	.12	.19	2	1
C 8+50E 25+50N	1	9	4	77	.3	6	15	980	4.26	2	8	ND	4	63	.2	3	3	98	1.06	.108	10	32	1.65	43	.24	3	2.31	.05	.06	2	5
C 8+50E 25+75N	1	8	9	91	.3	4	15	922	4.63	2	8	ND	2	75	.3	3	3	113	1.54	.114	8	19	1.40	60	.23	3	2.83	.26	.17	2	6
C 8+50E 26+00N	1	13	9	59	.3	3	9	740	3.57	2	8	ND	2	107	.2	3	3	82	1.10	.102	10	28	1.11	61	.20	3	1.94	.07	.08	2	10
C 8+50E 26+25N	4	67	13	94	.3	114	18	948	5.60	20	8	ND	2	29	.2	3	3	75	.16	.107	10	77	1.65	172	.01	3	2.65	.02	.22	2	5
C 8+50E 26+50N	1	9	3	61	.3	6	12	735	4.47	2	8	ND	2	142	.2	3	3	121	1.90	.158	7	20	.89	69	.17	3	2.34	.39	.12	2	22
C 8+50E 26+75N	1	16	9	89	.3	3	15	871	4.58	2	8	ND	3	47	.2	3	3	100	.63	.105	13	23	1.51	114	.16	4	2.11	.08	.19	2	8
C 8+50E 27+00N	1	15	6	72	.3	3	11	1141	4.48	2	8	ND	3	66	.2	3	3	125	1.13	.113	10	31	1.20	99	.18	3	1.86	.13	.15	2	9
C 8+50E 27+25N	2	3	7	51	.3	2	9	668	3.97	2	8	ND	7	25	.2	3	3	57	.50	.084	22	20	.93	122	.10	3	1.69	.06	.28	2	17
C 8+50E 27+50N	1	112	5	87	.3	17	28	1221	7.62	2	8	ND	2	69	.2	3	3	298	2.41	.226	4	87	2.92	40	.30	6	3.96	.03	.06	2	21
C 8+50E 27+75N	19	75	24	12	1.1	33	5	332	4.55	57	8	ND	2	6	.2	5	3	159	.14	.106	4	56	1.12	38	.01	3	1.77	.01	.25	2	11
C 8+50E 28+00N	1	39	7	52	.3	5	13	654	5.56	2	8	ND	2	79	.2	3	3	132	1.05	.128	8	28	.88	79	.18	3	1.92	.22	.15	2	15
C 8+50E 28+25N	1	18	5	52	.3	4	18	1034	5.28	2	8	ND	2	97	.2	3	3	115	1.55	.134	6	19	1.21	156	.18	3	2.60	.24	.20	2	18
C 8+50E 28+50N	1	20	3	43	.3	7	12	1222	4.16	6	8	ND	2	48	.2	3	3	68	2.93	.103	12	38	1.16	109	.14	3	2.09	.08	.24	2	28
C 8+50E 28+75N	1	33	3	61	.3	2	53	856	5.23	2	8	ND	2	69	.2	3	3	118	.92	.130	7	17	1.34	88	.20	3	2.26	.10	.17	2	19
C 8+50E 29+00N	1	59	5	62	.3	7	13	954	4.74	11	8	ND	2	164	.3	3	3	138	2.51	.130	8	26	1.13	88	.18	3	3.21	.49	.16	2	20
C 8+50E 29+25N	1	63	3	55	.3	5	11	893	5.06	15	8	ND	3	66	.2	3	3	98	1.14	.122	7	28	1.22	80	.22	3	2.89	.21	.22	2	110
C 8+50E 29+50N	1	16	6	62	.3	8	11	1047	5.10	9	8	ND	2	46	.2	3	3	140	1.09	.125	8	28	1.70	81	.18	3	2.72	.10	.15	2	4
C 8+50E 29+75N	2	43	9	34	.3	4	9	655	2.26	2	8	ND	2	172	.3	3	3	64	2.32	.137	7	23	.66	110	.13	3	3.42	.51	.11	2	5
C 8+50E 30+00N	1	31	5	44	.3	5	15	764	3.14	9	8	ND	2	56	.2	3	3	81	2.13	.137	6	35	.73	43	.15	3	2.43	.11	.13	2	19
C 9+00E 23+00N	1	1	3	61	.3	8	25	1088	7.36	2	8	ND	3	94	.2	3	3	169	1.91	.109	2	25	1.57	210	.14	3	3.10	.34	.27	4	31
MM 11+50E 27+50	1	2620	3	46	.3	8	31	1239	6.04	29	8	ND	2	12	.2	3	7	53	.78	.110	6	12	1.68	61	.09	3	2.81	.01	.33		

CERTIFICATE OF ASSAY AK 97 - 976

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

#####

ATTENTION: DINO CREMONESE

No. of samples received: 104

Sample Type: Core

PROJECT #: Clone

SHIPMENT #: CL-1

P.O. #: Not given

Samples submitted by: Dale Roberts

ET #.	Tag #	Au (g/t)	Au (oz/t)	As (%)	Co (%)
1	59761	12.64	0.369		
4	59754				0.027
14	59764	1.54	0.045		
18	59768	1.78	0.052		
28	59778				0.031
29	59779	2.83	0.083		0.056
30	59780	6.14	0.179		0.058
34	59784	6.45	0.188		0.049
35	59785				0.057
36	59786				0.031
40	59790	14.08	0.411	1.13	0.154
41	59791	2.25	0.066		
52	59802	1.34	0.039		
54	59804	2.03	0.059		
80	59830	3.18	0.093		0.052
81	59831				0.031
82	59832	11.13	0.325		0.066
87	59837	1.18	0.034		0.026
88	59838	2.78	0.081		
89	59839	1.45	0.042		
95	59845	1.42	0.041		

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

TEUTON RESOURCES CORPORATION AK 97 - 976

ET #.	Tag #	Au (g/t)	Au (oz/t)	As (%)	Co (%)
96	59846	3.06	0.089		
97	59847				0.064
98	59848	13.84	0.404		0.086
99	59849	41.80	1.219		0.094
100	59850				0.048
101	59851	9.92	0.289		0.096
102	59852	1.58	0.046		
103	59853	3.64	0.106		
Standard:					
	Su/a				0.041
	CD-1			0.66	
	STD-M	1.64	0.048		

XLS/97Teuton

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

CERTIFICATE OF ASSAY AK 97 - 974

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

11-Sep-97

ATTENTION: DINO CREMONESE

No. of samples received: 41

Sample Type: Core

PROJECT #: Clone

SHIPMENT #: CL-2

P.O.#: Not given

Samples submitted by: Dale Roberts

ET #.	Tag #	Au (g/t)	Au (oz/t)	Co (%)
1	59855	1.27	0.037	-
11	59865	8.44	0.246	0.223
12	59866	2.68	0.078	0.039
13	59867	1.12	0.033	0.061
14	59868	32.90	0.959	0.320
15	59869	-	-	0.061
18	59872	1.01	0.029	-
19	59873	12.03	0.351	-

QC/DATA:

Resplit:

R/S 1 59855 1.35 0.039 -

Repeat:

1 59855 1.23 0.036 -

Standard:

Sula - - 0.041

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

XLS/97Teuton

10-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 8T4

Phone: 804-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK-97-974

TEUTON RESOURCES CORPORATION
508-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DIMO CREMONESE

No. of samples received: 41
Sample Type: CORE
PROJECT #: CLONE
SHIPMENT #: CL-2
Samples submitted by: DALE ROBERTS

Values in ppm unless otherwise reported

Et#	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Tl%	U	V	W	Y	Zn
1	59855	>1000	0.2	2.19	70	110	<5	2.84	<1	73	18	154	3.85	<10	1.82	741	2	0.03	<1	1520	<2	5	<20	60	0.02	<10	38	<10	1	55
2	59856	40	<0.2	1.80	15	315	<5	3.83	<1	23	22	140	3.08	<10	1.23	732	2	0.05	<1	1530	<2	15	<20	91	0.03	<10	43	<10	2	41
3	59857	215	0.2	1.57	20	415	<5	3.48	<1	25	15	125	3.01	<10	1.14	782	2	0.03	<1	1420	4	5	<20	95	0.02	<10	38	<10	2	37
4	59858	260	0.2	1.58	45	85	<5	3.81	<1	42	9	161	2.82	<10	1.04	778	1	0.02	<1	1480	20	10	<20	88	0.02	<10	31	<10	2	78
5	59859	15	0.6	1.86	30	90	<5	5.21	1	19	12	145	3.08	<10	1.14	874	<1	0.02	<1	1510	52	<5	<20	94	0.02	<10	35	<10	2	82
6	59860	205	<0.2	1.96	90	225	<5	2.39	<1	87	8	100	3.05	10	1.29	727	1	0.01	<1	1620	4	5	<20	31	0.01	<10	23	<10	3	92
7	59861	225	<0.2	1.79	80	110	<5	2.41	<1	73	10	258	3.28	<10	1.18	837	2	0.02	<1	1610	2	<5	<20	49	0.02	<10	33	<10	<1	74
8	59862	780	<0.2	1.86	80	195	<5	1.70	<1	80	14	204	3.74	<10	1.12	454	2	0.02	<1	1620	6	<5	<20	43	0.02	<10	44	<10	<1	42
9	59863	220	<0.2	2.12	65	135	<5	1.48	<1	63	29	200	4.83	<10	1.48	525	3	0.02	<1	1610	<2	<5	<20	38	0.02	<10	56	<10	<1	50
10	59864	270	<0.2	2.22	115	115	<5	1.20	<1	121	13	173	4.73	<10	1.73	535	3	0.02	<1	1430	<2	<5	<20	28	<0.01	<10	51	<10	<1	82
11	59865	>1000	9.2	2.53	1696	95	<5	2.56	<1	1688	20	1842	>10	<10	1.72	1113	10	0.01	<1	1320	18	<5	<20	63	0.01	<10	79	10	<1	138
12	59866	>1000	1.6	2.41	375	100	<5	3.08	<1	352	20	1114	9.99	<10	1.82	802	9	0.01	<1	1240	<2	<5	<20	105	0.01	<10	84	<10	<1	178
13	59867	>1000	0.8	2.52	715	110	<5	2.39	<1	578	19	248	8.41	<10	1.83	783	4	0.01	<1	1490	<2	<5	<20	84	0.02	<10	82	<10	<1	150
14	59868	>1000	11.4	2.22	3540	90	<5	3.42	<1	2711	25	3458	>10	<10	1.74	913	17	0.01	<1	1380	8	<5	<20	152	0.03	<10	111	<10	<1	224
15	59869	865	0.8	1.88	680	105	<5	2.28	<1	549	9	701	4.84	<10	1.24	588	3	0.01	<1	1480	<2	<5	<20	85	0.05	<10	45	<10	<1	88
16	59870	215	<0.2	2.20	95	145	<5	2.35	<1	80	19	148	5.29	<10	1.50	645	2	0.02	<1	1830	2	<5	<20	86	0.03	<10	71	<10	1	86
17	59871	315	<0.2	1.87	15	95	5	1.34	<1	44	20	30	4.01	<10	1.43	737	1	0.03	<1	1580	10	10	<20	30	0.05	<10	49	<10	2	105
18	59872	>1000	0.2	1.95	65	335	10	3.55	4	68	21	34	5.26	<10	1.26	1430	2	0.01	<1	1440	6	<5	<20	81	0.04	<10	70	<10	2	550
19	59873	>1000	1.0	2.49	<5	180	5	1.88	4	44	11	53	7.11	<10	1.81	1287	3	0.01	<1	1580	<2	<5	<20	38	0.05	<10	84	<10	<1	988
20	59874	230	<0.2	1.90	10	105	5	1.64	<1	20	14	55	4.45	<10	1.35	778	2	0.02	<1	1540	<2	<5	<20	37	0.04	<10	52	<10	<1	258
21	59875	415	1.2	2.04	135	120	<5	1.73	<1	91	18	549	4.38	<10	1.45	824	3	0.02	<1	1580	4	5	<20	39	0.01	<10	48	<10	<1	175
22	59876	95	<0.2	2.13	65	90	<5	1.23	<1	28	7	184	3.83	<10	1.39	894	2	0.04	<1	1640	2	5	<20	21	0.01	<10	48	<10	1	103
23	59877	30	<0.2	2.20	85	140	<5	1.80	<1	37	8	143	4.13	<10	1.44	1033	3	0.03	<1	1510	8	<5	<20	30	0.01	<10	43	<10	<1	71
24	59878	25	0.2	2.13	45	95	<5	2.33	<1	23	7	188	4.08	<10	1.28	888	4	0.04	<1	1580	38	<5	<20	40	0.03	<10	57	<10	2	138
25	59879	10	<0.2	1.73	70	85	<5	1.79	<1	31	17	130	3.87	<10	0.88	579	8	0.03	<1	1570	8	<5	<20	25	0.03	<10	49	10	2	88

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-974

ECO-TECH LABORATORIES LTD.

Et#	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Tl%	U	V	W	Y	Zn
26	59880	5	<0.2	1.57	40	75	<5	4.85	<1	18	11	47	2.89	<10	0.77	870	2	0.02	<1	1550	<2	<5	<20	83	0.04	<10	38	<10	6	58
27	59881	5	<0.2	1.77	35	60	<5	2.74	<1	11	18	80	3.84	<10	1.13	713	6	0.04	<1	1550	4	5	<20	90	0.07	<10	60	<10	3	44
28	59882	60	0.8	1.97	35	85	<5	2.64	2	18	15	381	4.23	<10	1.17	751	7	0.04	<1	1800	18	<5	<20	50	0.08	<10	55	<10	3	128
29	59883	45	0.4	1.59	35	85	<5	3.54	3	21	10	588	3.31	<10	0.88	754	3	0.02	<1	1580	6	5	<20	80	0.05	<10	48	<10	3	240
30	59884	5	<0.2	1.88	10	60	<5	3.34	<1	9	10	28	3.50	<10	1.22	751	<1	0.04	<1	1580	<2	5	<20	71	0.08	<10	51	<10	3	40
31	59885	5	<0.2	1.98	10	155	5	2.77	<1	7	12	20	3.55	<10	1.22	770	<1	0.05	<1	1800	<2	<5	<20	59	0.07	<10	59	<10	3	39
32	59886	5	<0.2	1.92	20	80	<5	2.83	<1	7	15	25	3.74	<10	1.30	724	<1	0.05	<1	1580	<2	5	<20	52	0.07	<10	67	<10	2	49
33	59887	5	<0.2	1.54	15	140	<5	3.42	<1	8	18	15	3.18	<10	0.89	889	<1	0.08	<1	1530	<2	5	<20	77	0.05	<10	82	<10	2	44
34	59888	5	<0.2	1.87	15	55	<5	4.15	<1	8	11	32	3.48	<10	1.20	770	<1	0.04	<1	1550	<2	10	<20	81	0.08	<10	60	<10	4	47
35	59889	5	<0.2	1.84	20	65	<5	2.87	<1	7	14	7	3.80	<10	1.18	858	<1	0.05	<1	1800	<2	<5	<20	81	0.08	<10	68	<10	1	48
36	59890	10	<0.2	2.15	40	55	<5	2.73	<1	11	8	35	3.87	<10	1.38	710	1	0.04	<1	1580	<2	15	<20	52	0.07	<10	57	<10	2	39
37	59891	5	<0.2	2.28	255	45	5	3.08	<1	11	9	51	4.35	<10	1.57	715	<1	0.05	<1	1530	<2	<5	<20	61	0.07	<10	67	<10	2	33
38	59892	5	<0.2	2.03	270	50	<5	2.43	<1	10	10	39	3.90	<10	1.41	814	<1	0.04	<1	1580	2	5	<20	44	0.08	<10	58	<10	3	29
39	59893	5	<0.2	2.12	110	85	<5	3.03	<1	9	10	83	3.80	<10	1.47	816	<1	0.05	<1	1510	<2	10	<20	70	0.08	<10	63	<10	2	30
40	59894	95	<0.2	2.26	35	70	<5	3.87	<1	8	9	84	3.79	<10	1.55	731	<1	0.05	<1	1530	<2	15	<20	68	0.07	<10	57	<10	3	47

41	59885	10	<0.2	1.88	35	185	<5	8.96	<1	8	3	15	2.70	<10	1.22	1075	<1	0.02	<1	1420	<2	15	<20	145	0.03	<10	23	<10	8	47
----	-------	----	------	------	----	-----	----	------	----	---	---	----	------	-----	------	------	----	------	----	------	----	----	-----	-----	------	-----	----	-----	---	----

QC/DATA:

Repeat:																															
1	59855	>1000	0.4	2.18	80	110	<5	2.61	<1	74	20	148	3.84	<10	1.60	734	2	0.03	<1	1560	<2	10	<20	56	0.02	<10	39	<10	1	56	
36	59890	10	<0.2	2.18	45	50	<5	2.76	<1	11	9	35	3.99	<10	1.42	719	<1	0.04	<1	1570	<2	5	<20	51	0.07	<10	57	<10	2	38	

Repeat:																															
1	59855	>1000	0.2	2.25	80	105	<5	2.63	<1	74	18	154	3.88	<10	1.63	745	3	0.03	<1	1800	4	10	<20	53	0.02	<10	40	10	2	57	
10	59884	275	<0.2	2.25	120	120	<5	1.21	<1	122	13	178	4.75	<10	1.74	535	3	0.02	<1	1430	<2	<5	<20	28	<0.01	<10	51	<10	<1	84	
19	59873	>1000	1.0	2.55	10	185	10	1.85	4	43	11	53	7.05	<10	1.83	1284	3	0.01	<1	1560	<2	<5	<20	36	0.05	<10	85	<10	<1	925	
36	59890	5	<0.2	2.22	50	50	<5	2.74	<1	11	9	35	3.99	<10	1.42	719	<1	0.04	<1	1580	<2	<5	<20	53	0.07	<10	58	<10	3	38	

Standard:																															
GEO'97		150	1.0	1.78	80	155	<5	1.87	<1	19	84	81	4.07	<10	0.94	684	<1	0.03	23	630	18	<5	<20	62	0.11	<10	78	<10	4	68	
GEO'97		.	1.2	1.85	80	160	<5	1.83	<1	19	59	84	4.15	<10	0.97	686	<1	0.03	24	660	18	<5	<20	66	0.12	<10	80	<10	5	64	

df/974
XLS/97Teuton

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

11-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK 97 - 975

TEUTON RESOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 60
Sample Type: Core
PROJECT #: Clone
SHIPMENT #: CL-3
P.O.#: Not given
Samples submitted by: Dale Roberts

Values in ppm unless otherwise reported

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	58896	130	<0.2	1.71	50	120	<5	4.54	<1	10	9	87	3.18	<10	1.14	740	8	0.02	<1	1480	<2	<5	<20	90	0.02	<10	27	<10	3	64
2	58897	5	<0.2	1.60	60	75	<5	2.69	<1	10	15	88	3.49	<10	0.89	578	34	0.04	<1	1510	4	<5	<20	88	0.02	<10	38	<10	2	86
3	58898	10	<0.2	1.66	60	105	<5	2.73	<1	11	15	104	3.59	<10	1.02	852	13	0.04	<1	1560	24	5	<20	63	0.05	<10	47	<10	3	83
4	58899	10	<0.2	1.71	35	105	<5	2.95	<1	10	12	111	3.57	<10	1.11	736	5	0.04	<1	1540	20	<5	<20	68	0.05	<10	47	<10	3	70
5	58900	195	0.4	1.82	60	105	<5	2.96	<1	17	13	248	3.59	<10	1.09	713	<1	0.04	<1	1540	14	5	<20	76	0.05	<10	40	<10	3	72
6	58901	55	<0.2	1.85	40	85	<5	4.52	1	14	12	205	3.67	<10	1.18	914	4	0.04	<1	1520	26	<5	<20	109	0.06	<10	46	<10	4	82
7	58902	60	<0.2	1.88	35	125	<5	3.98	<1	14	15	175	3.64	<10	1.26	839	2	0.04	<1	1470	2	<5	<20	86	0.05	<10	44	<10	3	90
8	58903	300	1.0	1.87	45	180	<5	4.52	2	33	7	688	3.94	<10	1.36	942	3	0.02	<1	1530	4	5	<20	96	0.02	<10	36	10	2	134
9	58904	215	<0.2	1.94	120	220	<5	3.02	<1	93	11	278	3.67	<10	1.29	764	2	0.02	<1	1550	<2	<5	<20	69	0.03	<10	35	<10	3	151
10	58905	345*	0.4	1.93	240	635	<5	1.88	<1	148	10	220	3.65	<10	1.34	860	2	0.02	<1	1620	<2	10	<20	88	0.03	<10	35	<10	2	198
11	58906	125	<0.2	2.02	185	765	<5	2.56	<1	115	12	132	3.62	<10	1.43	758	2	0.01	<1	1580	<2	15	<20	89	0.02	<10	37	<10	2	191
12	58907	335	0.4	1.53	125	870	<5	2.96	<1	87	19	364	3.02	<10	1.09	780	2	0.02	<1	1630	4	15	<20	94	0.01	<10	38	<10	2	219
13	58908	30	<0.2	1.79	145	90	<5	1.06	<1	155	12	132	3.26	<10	1.27	530	1	0.02	<1	1600	<2	<5	<20	30	0.02	<10	35	<10	2	176
14	58909	>1000	1.0	1.95	260	100	<5	2.41	<1	233	19	444	4.34	<10	1.15	821	2	0.01	<1	1440	8	<5	<20	87	0.03	<10	54	<10	<1	128
15	58910	145	<0.2	1.85	120	110	<5	1.67	<1	118	13	144	3.62	<10	1.29	552	1	0.02	<1	1580	<2	<5	<20	50	0.04	<10	46	<10	2	90
16	58911	265	<0.2	1.88	125	100	<5	1.84	<1	116	19	103	3.62	<10	1.35	833	2	0.02	<1	1800	<2	5	<20	49	0.02	<10	42	<10	2	119
17	58912	115	0.4	1.98	45	95	<5	1.00	<1	60	7	116	3.93	<10	1.41	729	2	0.02	<1	1550	<2	5	<20	20	<0.01	<10	42	<10	1	102
18	58913	385	<0.2	1.90	90	85	15	2.00	<1	139	7	25	3.30	<10	1.35	709	1	0.02	<1	1850	4	5	<20	32	<0.01	<10	28	10	3	138
19	58914	15	<0.2	1.80	30	1250	<5	6.89	<1	43	9	8	2.47	<10	1.15	1015	<1	0.01	<1	1540	<2	5	<20	182	0.02	<10	22	<10	7	67
20	58915	110	<0.2	1.38	20	205	<5	5.24	<1	18	10	20	2.32	<10	0.80	780	<1	0.01	<1	1550	<2	5	<20	118	0.03	<10	21	<10	5	47
21	58916	30	<0.2	1.40	10	300	<5	4.55	<1	10	8	65	2.30	<10	0.84	808	<1	0.02	<1	1550	4	<5	<20	107	0.02	<10	25	<10	3	35
22	58917	5	<0.2	1.73	15	180	<5	3.63	<1	7	4	4	2.69	<10	1.16	801	<1	0.02	<1	1580	4	10	<20	74	0.01	<10	25	10	3	40
23	58918	10	<0.2	1.80	10	110	<5	4.51	<1	6	22	7	2.52	<10	0.97	830	1	0.03	<1	1590	<2	5	<20	101	0.01	<10	27	<10	2	70
24	58919	15	<0.2	1.67	5	95	<5	3.91	<1	6	15	2	2.87	<10	1.09	881	1	0.03	<1	1580	<2	5	<20	84	0.02	<10	34	<10	3	39
25	58920	15	<0.2	1.46	5	100	<5	3.86	<1	5	10	3	1.97	<10	0.80	854	<1	0.02	<1	1600	4	5	<20	75	0.01	<10	22	<10	4	67

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK 97 - 975

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	58921	10	<0.2	1.39	10	190	<5	1.52	<1	11	19	28	4.38	<10	0.97	967	<1	0.05	<1	1550	26	<5	<20	44	0.08	<10	67	<10	<1	96
27	58922	20	<0.2	1.11	10	70	<5	2.14	<1	8	36	14	4.28	<10	0.73	838	1	0.05	<1	1500	8	<5	<20	82	0.05	<10	64	<10	<1	85
28	58923	45	<0.2	1.28	10	95	<5	1.32	<1	33	35	18	4.07	<10	0.85	877	3	0.04	<1	1580	8	<5	<20	49	0.05	<10	56	<10	<1	109
29	58924	10	<0.2	1.25	10	95	5	1.44	<1	66	18	30	4.32	<10	0.91	895	1	0.04	<1	1630	4	<5	<20	31	0.05	<10	70	<10	<1	206
30	58925	615	<0.2	1.42	10	115	5	1.75	<1	40	32	42	4.84	<10	0.98	796	2	0.03	<1	1570	18	<5	<20	38	0.05	<10	72	<10	<1	194
31	58926	20	<0.2	1.28	15	100	5	1.30	<1	17	16	26	4.34	<10	0.94	766	1	0.03	<1	1600	10	<5	<20	29	0.05	<10	74	<10	<1	150
32	58927	10	<0.2	1.18	10	85	5	1.44	<1	18	26	8	3.87	<10	0.75	727	2	0.03	<1	1700	4	<5	<20	33	0.05	<10	49	<10	<1	127
33	58928	15	0.4	1.19	5	90	<5	2.03	<1	20	17	157	3.78	<10	0.80	797	<1	0.03	<1	1590	10	<5	<20	56	0.05	<10	58	<10	<1	129
34	58929	45	<0.2	1.46	15	95	5	0.91	<1	29	17	14	4.47	<10	1.02	798	2	0.02	<1	1680	8	<5	<20	21	0.06	<10	63	<10	<1	280
35	58930	150	<0.2	1.43	10	90	<5	2.08	1	25	14	51	4.44	<10	1.02	951	<1	0.03	<1	1600	10	5	<20	32	0.05	<10	68	<10	<1	189
36	58931	10	0.2	1.57	10	160	<5	1.86	<1	27	24	337	3.78	<10	0.95	895	2	0.05	<1	1610	8	10	<20	42	0.06	<10	75	<10	1	86
37	58932	5	1.0	1.55	20	175	<5	1.94	<1	25	28	803	3.87	<10	1.01	932	3	0.06	<1	1620	28	10	<20	55	0.05	<10	105	<10	<1	82
38	58933	5	<0.2	1.47	20	95	10	1.88	<1	16	18	25	3.66	<10	1.08	899	<1	0.05	<1	1620	12	5	<20	41	0.05	<10	60	10	2	124
39	58934	10	<0.2	1.43	20	145	5	1.65	<1	14	20	32	4.79	<10	1.13	793	2	0.04	<1	1590	8	<5	<20	43	0.05	<10	89	<10	<1	88
40	58935	5	<0.2	1.43	10	135	<5	2.58	<1	8	15	15	4.02	<10	1.21	783	1	0.05	<1	1570	2	5	<20	63	0.06	<10	80	<10	<1	37

41	59936	5	<0.2	1.70	10	125	10	2.57	<1	13	19	3	3.79	<10	1.29	775	1	0.08	<1	1590	4	5	<20	65	0.06	<10	89	<10	1	44
42	59937	40	<0.2	1.88	10	80	5	2.38	<1	13	12	15	3.74	<10	1.37	738	1	0.05	<1	1570	4	5	<20	54	0.08	<10	66	<10	<1	37
43	59938	5	<0.2	1.72	10	105	5	1.71	<1	11	17	14	3.87	<10	1.55	857	1	0.05	<1	1840	4	10	<20	43	0.07	<10	89	<10	<1	41
44	59939	5	<0.2	1.52	10	75	<5	2.55	<1	6	18	22	3.30	<10	1.32	865	<1	0.07	<1	1800	2	5	<20	62	0.06	<10	77	<10	<1	69
45	59940	5	<0.2	1.50	15	75	<5	2.11	<1	14	18	5	3.03	<10	1.30	825	<1	0.07	<1	1850	2	5	<20	81	0.06	<10	71	<10	<1	85
46	59941	15	<0.2	1.69	10	70	<5	1.93	<1	9	14	8	3.25	<10	1.54	896	<1	0.07	<1	1560	2	10	<20	49	0.06	<10	85	<10	<1	109
47	59942	10	<0.2	1.66	15	75	<5	1.99	<1	7	20	87	3.28	<10	1.36	860	<1	0.08	<1	1570	2	5	<20	64	0.06	<10	84	<10	<1	40
48	59943	50	<0.2	1.41	10	80	<5	2.70	<1	11	9	45	3.35	<10	1.19	898	<1	0.06	<1	1570	4	5	<20	58	0.05	<10	70	<10	<1	71
49	59944	40	<0.2	1.81	10	80	<5	3.05	1	14	13	28	3.08	<10	1.27	824	<1	0.06	<1	1580	4	5	<20	53	0.08	<10	53	<10	1	206
50	59945	45	<0.2	1.77	10	95	<5	2.13	<1	10	10	8	3.38	<10	1.33	727	<1	0.05	<1	1570	4	10	<20	44	0.06	<10	48	<10	1	86
51	59946	305	<0.2	1.58	10	90	5	3.10	<1	17	11	8	3.11	<10	1.02	704	<1	0.04	<1	1590	<2	5	<20	49	0.06	<10	45	<10	2	89
52	59947	315	<0.2	1.41	<5	130	5	1.86	<1	20	6	8	3.35	<10	0.91	822	<1	0.03	<1	1820	4	<5	<20	42	0.05	<10	46	<10	1	89
53	59948	45	<0.2	1.27	<5	125	5	1.80	<1	20	16	10	3.21	<10	0.89	562	<1	0.04	<1	1850	8	5	<20	40	0.06	<10	48	<10	2	88
54	59949	5	<0.2	1.59	5	110	<5	2.02	<1	7	10	80	3.74	<10	1.22	574	<1	0.06	<1	1580	4	10	<20	43	0.08	<10	56	<10	1	87
55	59950	5	<0.2	1.60	5	125	<5	1.92	<1	7	13	18	3.78	<10	1.28	555	1	0.05	<1	1850	4	10	<20	39	0.06	<10	58	<10	2	89
56	59951	10	<0.2	1.65	5	105	<5	2.47	<1	8	10	43	4.01	<10	1.28	839	<1	0.04	<1	1800	4	5	<20	42	0.06	<10	52	<10	1	88
57	59952	285	<0.2	1.58	<5	85	<5	2.10	<1	23	8	19	3.20	<10	1.10	580	<1	0.03	<1	1840	6	10	<20	40	0.05	<10	45	<10	2	75
58	59953	65	<0.2	1.42	5	70	<5	2.46	<1	21	8	16	3.31	<10	1.11	629	<1	0.02	<1	1820	4	<5	<20	44	0.05	<10	41	<10	3	79
59	59954	5	<0.2	1.67	15	135	5	2.09	<1	10	7	44	3.53	<10	1.44	731	<1	0.03	<1	1860	2	5	<20	45	0.05	<10	43	<10	2	70
60	59955	5	0.4	1.54	5	115	<5	2.73	<1	8	4	183	3.29	<10	1.27	827	<1	0.03	<1	1530	4	5	<20	63	0.05	<10	44	<10	3	54

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK 97 - 975

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
QC/DATA:																															
<i>Resplit:</i>																															
R/S 1	59896	100	<0.2	1.81	50	115	<5	4.77	<1	10	9	87	3.21	<10	1.15	765	5	0.02	<1	1530	<2	5	<20	90	0.02	<10	28	<10	3	68	
<i>Repeat:</i>																															
1	59896	125	<0.2	1.88	55	115	<5	4.51	<1	10	12	87	3.19	<10	1.13	738	6	0.02	<1	1520	<2	5	<20	88	0.02	<10	28	<10	4	66	
10	59905	250	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
19	59914	15	<0.2	1.85	25	1165	5	8.28	<1	38	7	7	2.28	<10	1.08	930	<1	0.01	<1	1400	<2	15	<20	152	0.02	<10	20	<10	6	59	
36	59931	10	0.2	1.54	15	145	<5	1.86	<1	27	24	338	3.77	<10	0.85	893	<1	0.05	<1	1820	10	10	<20	38	0.06	<10	74	<10	1	66	
45	59940	5	<0.2	1.49	15	70	<5	2.15	<1	14	19	4	3.10	<10	1.30	835	<1	0.07	<1	1890	6	<5	<20	58	0.06	<10	70	<10	1	101	
54	59949	5	<0.2	1.48	5	100	<5	2.05	<1	8	9	63	3.75	<10	1.22	580	<1	0.04	<1	1830	4	<5	<20	38	0.06	<10	53	<10	1	89	
<i>Standard:</i>																															
GEO'97		140	1.2	1.76	65	145	<5	1.83	<1	20	84	80	3.92	<10	0.98	852	<1	0.02	21	840	18	<5	<20	54	0.10	<10	72	<10	6	70	
GEO'97		155	1.2	1.70	65	155	<5	1.87	<1	18	84	83	4.01	<10	0.98	875	<1	0.03	21	860	18	<5	<20	56	0.10	<10	73	<10	6	84	

NOTE: * = Metallic gold suspected
Screen Assay recommended

df/S75
XLS/S7Teuton

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

11-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AS-978

TEUTON RESOURCES CORPORATION
508-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 104
Sample Type: CORE
PROJECT #: CLONE
SHIPMENT #: CL-1
Samples submitted by: DALE ROBERTS

Values in ppm unless otherwise reported

Et#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	59751	>1000	1.0	2.03	15	110	10	2.09	5	40	13	48	7.45	<10	1.40	1498	5	0.01	2	1310	8	<5	<20	43	0.04	<10	87	<10	<1	1276
2	59752	130	<0.2	1.73	5	105	5	1.20	<1	28	17	29	4.72	<10	1.31	891	2	0.02	<1	1520	2	<5	<20	29	0.05	<10	57	<10	<1	371
3	59753	115	0.8	1.79	130	80	<5	0.80	<1	88	27	472	4.90	<10	1.31	889	5	0.02	2	1550	14	<5	<20	20	0.02	<10	60	<10	<1	132
4	59754	555	2.4	2.30	315	90	<5	1.89	<1	257	27	807	5.12	<10	1.80	748	3	0.02	7	1900	14	<5	<20	36	0.03	<10	88	<10	<1	150
5	59755	15	1.0	2.19	115	100	<5	1.58	<1	97	23	762	4.31	<10	1.57	780	4	0.03	3	1880	8	10	<20	28	0.04	<10	53	<10	1	114
6	59756	10	<0.2	3.29	30	105	<5	5.95	<1	52	17	61	6.77	<10	2.80	1751	2	0.02	14	1580	<2	<5	<20	108	0.10	<10	123	<10	1	125
7	59757	5	<0.2	1.94	30	90	<5	2.15	<1	23	16	115	3.75	<10	1.41	827	4	0.03	<1	1540	4	10	<20	38	0.07	<10	47	<10	3	60
8	59758	10	<0.2	1.86	45	75	<5	2.13	<1	13	13	92	4.19	<10	1.31	819	5	0.04	1	1580	14	<5	<20	38	0.08	<10	70	<10	3	51
9	59759	15	<0.2	1.89	40	55	<5	2.24	<1	13	16	83	4.24	<10	1.29	778	5	0.04	<1	1810	10	<5	<20	37	0.08	<10	74	<10	3	58
10	59760	5	<0.2	2.03	40	80	<5	2.36	<1	14	21	87	4.22	<10	1.42	885	5	0.05	<1	1560	22	<5	<20	42	0.08	<10	69	<10	3	67
11	59761	240	<0.2	1.78	40	90	<5	3.77	<1	31	18	114	4.13	<10	1.18	848	5	0.03	3	1480	8	5	<20	68	0.08	<10	48	<10	3	105
12	59762	25	<0.2	1.13	30	110	<5	3.61	1	19	12	81	2.81	<10	0.55	570	3	0.02	1	1520	14	<5	<20	68	0.07	<10	34	<10	5	110
13	59763	25	<0.2	1.51	80	105	<5	4.17	<1	44	14	15	3.08	<10	0.85	885	<1	0.03	1	1610	<2	<5	<20	83	0.07	<10	40	<10	4	107
14	59764	>1000	<0.2	1.89	90	90	<5	3.98	<1	77	16	123	3.84	<10	1.28	894	<1	0.02	1	1320	4	<5	<20	69	0.07	<10	39	<10	4	208
15	59765	5	0.4	1.54	45	105	<5	3.87	<1	17	19	204	3.22	<10	0.88	750	<1	0.03	<1	1420	8	<5	<20	65	0.08	<10	38	<10	5	71
16	59766	110	<0.2	1.87	80	50	<5	3.84	<1	14	14	65	3.93	<10	1.35	802	1	0.03	<1	1540	14	<5	<20	63	0.08	<10	53	<10	3	85
17	59767	10	<0.2	2.14	100	80	<5	2.29	<1	50	15	78	4.30	<10	1.44	895	2	0.04	<1	1820	8	<5	<20	44	0.07	<10	61	<10	2	72
18	59768	>1000	<0.2	2.15	585	45	<5	2.55	<1	120	9	98	4.90	<10	1.50	705	3	0.03	<1	1730	24	<5	<20	42	0.07	<10	78	<10	2	83
19	59769	5	0.2	1.81	85	70	10	3.44	<1	15	13	78	4.07	<10	1.13	758	12	0.04	<1	1880	22	<5	<20	57	0.07	<10	55	<10	4	50
20	59770	5	<0.2	1.94	90	70	<5	3.50	<1	31	18	130	3.90	<10	1.31	748	8	0.03	1	1480	14	<5	<20	68	0.08	<10	45	<10	3	50
21	59771	5	<0.2	1.82	100	215	<5	4.48	<1	81	18	68	3.88	<10	1.35	858	3	0.02	<1	1280	8	<5	<20	98	0.07	<10	50	<10	5	88
22	59772	5	<0.2	2.06	110	55	<5	2.73	<1	51	19	116	4.53	<10	1.46	755	8	0.04	2	1390	12	<5	<20	82	0.08	<10	58	<10	4	79
23	59773	5	<0.2	1.73	120	100	<5	2.45	<1	48	21	123	3.71	<10	1.10	827	11	0.06	<1	1450	24	<5	<20	58	0.08	<10	53	<10	5	82
24	59774	5	<0.2	2.12	155	90	<5	1.78	<1	70	18	102	3.88	<10	1.38	728	5	0.02	<1	1550	28	<5	<20	38	0.08	<10	48	<10	3	74
25	59775	5	<0.2	1.89	215	80	<5	2.57	<1	16	18	47	3.84	<10	1.37	780	6	0.05	<1	1550	4	5	<20	55	0.08	<10	58	<10	4	82

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS-978

ECO-TECH LABORATORIES LTD.

Et#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	59776	5	<0.2	1.91	55	155	<5	2.25	<1	13	11	26	3.32	<10	1.49	760	4	0.03	<1	1460	4	5	<20	52	0.08	<10	44	<10	4	81
27	59777	10	<0.2	2.01	235	95	<5	2.58	<1	153	15	140	3.74	<10	1.35	713	8	0.02	<1	1590	4	<5	<20	64	0.08	<10	42	<10	2	145
28	59778	475	0.4	1.90	1045	105	<5	2.05	<1	284	19	278	4.81	<10	1.30	702	13	0.03	<1	1380	8	<5	<20	51	0.08	<10	58	<10	<1	191
29	59779	>1000	0.8	1.48	6380	90	<5	3.07	<1	501	25	351	5.57	<10	1.04	713	15	0.03	<1	930	10	<5	<20	91	0.08	<10	55	<10	<1	140
30	59780	>1000	1.8	1.59	1510	105	<5	2.20	<1	548	21	1546	7.87	<10	1.19	685	20	0.01	<1	870	8	<5	<20	54	0.05	<10	72	<10	<1	234
31	59781	205	<0.2	1.68	285	140	<5	3.04	<1	137	25	380	3.83	<10	1.09	742	10	0.03	<1	1150	8	10	<20	67	0.08	<10	44	<10	5	127
32	59782	5	<0.2	1.83	120	80	<5	2.57	<1	85	15	125	2.80	<10	1.08	688	4	0.02	<1	1570	4	10	<20	51	0.05	<10	32	<10	4	74
33	59783	30	<0.2	1.78	110	170	<5	3.34	<1	87	18	138	3.08	<10	1.14	780	3	0.03	<1	1500	2	5	<20	73	0.08	<10	44	<10	4	73
34	59784	>1000	0.4	0.82	825	110	<5	2.43	<1	444	22	172	7.86	<10	0.49	417	8	0.01	<1	820	6	<5	<20	87	0.08	<10	58	<10	<1	54
35	59785	210	<0.2	1.17	815	80	<5	1.23	<1	447	44	153	5.12	<10	0.72	383	7	0.01	<1	880	4	<5	<20	38	0.04	<10	37	<10	<1	55
36	59786	205	<0.2	2.31	335	80	<5	2.17	<1	275	21	74	4.81	<10	1.71	797	2	0.02	<1	1080	<2	<5	<20	54	0.08	<10	45	<10	2	98
37	59787	305	<0.2	1.70	50	70	<5	3.74	<1	43	14	331	3.47	<10	1.23	777	2	0.02	<1	1400	2	10	<20	80	0.04	<10	43	<10	3	72
38	59788	180	0.2	1.88	60	90	<5	1.33	<1	36	19	588	3.28	<10	1.21	632	2	0.02	<1	1540	4	5	<20	25	0.01	<10	41	<10	2	86
39	59789	205	0.2	1.87	100	85	<5	0.87	<1	43	18	479	3.88	<10	1.27	480	2	0.02	<1	1440	14	<5	<20	20	0.01	<10	41	<10	2	83
40	59790	>1000	3.8	3.32	10000	65	<5	0.51	<1	1382	18	1231	>10	<10	2.24	788	125	0.01	<1	1880	44	<5	<20	16	0.01	20	180	<10	<1	88
41	59791	>1000	0.8	3.05	455	90	<5	0.87	<1	84	14	897	9.15	<10	2.13	758	10	0.01	1	1420	10	<5	<20	15	0.01	<10	129	<10	<1	85

42	59792	555	1.0	2.94	165	85	<5	0.54	<1	57	14	1759	7.55	<10	2.15	569	8	0.03	<1	1390	8	<5	<20	12	0.02	<10	88	<10	<1	81
43	59793	115	<0.2	2.80	145	95	<5	2.33	<1	33	20	172	8.30	<10	1.94	803	7	0.02	<1	1440	4	<5	<20	48	0.03	<10	85	<10	<1	88
44	59794	125	<0.2	2.77	95	80	<5	3.04	2	41	15	207	8.32	<10	2.13	898	8	0.02	<1	1480	<2	<5	<20	82	0.02	<10	89	<10	<1	84
45	59795	55	<0.2	2.68	80	55	<5	1.59	<1	48	5	490	8.82	<10	2.19	814	8	0.02	3	1790	2	<5	<20	37	0.01	<10	122	<10	<1	72
46	59796	15	<0.2	2.75	85	35	<5	2.68	<1	62	3	154	8.58	<10	2.22	871	5	0.02	2	1920	<2	<5	<20	49	<0.01	<10	104	<10	2	83
47	59797	60	1.2	3.35	50	55	<5	4.88	<1	45	7	409	8.18	<10	2.84	869	8	0.03	5	1820	8	<5	<20	102	0.01	<10	130	<10	<1	71
48	59798	105	1.4	2.82	90	80	<5	0.76	<1	33	8	324	5.89	<10	2.12	787	4	0.02	<1	2090	8	<5	<20	24	<0.01	<10	109	<10	5	47
49	59799	50	<0.2	2.52	55	105	<5	2.04	<1	24	4	205	8.13	<10	2.16	738	4	0.02	3	1860	<2	<5	<20	49	0.02	<10	101	<10	3	41
50	59800	15	<0.2	3.24	35	80	<5	3.23	<1	34	12	203	8.37	<10	2.77	874	5	0.02	7	1790	<2	<5	<20	70	0.03	<10	145	<10	<1	49
51	59801	50	<0.2	2.32	15	55	<5	6.77	<1	18	11	48	4.89	<10	1.99	1027	2	0.02	2	1850	<2	5	<20	138	0.01	<10	83	<10	5	33
52	59802	>1000	0.2	1.84	60	110	<5	1.84	4	53	20	67	4.84	<10	1.23	1062	4	0.02	<1	1370	12	<5	<20	36	0.03	<10	58	<10	2	308
53	59803	230	<0.2	1.72	40	155	10	4.17	11	44	22	21	9.70	<10	1.10	1780	6	0.01	2	1180	2	<5	<20	80	0.05	<10	117	<10	<1	803
54	59804	>1000	<0.2	1.43	15	115	<5	1.32	1	32	15	38	4.31	<10	1.09	883	2	0.02	<1	1300	4	<5	<20	33	0.03	<10	45	<10	<1	881
55	59805	45	<0.2	1.55	20	75	<5	1.11	<1	18	15	28	4.05	<10	1.24	712	2	0.02	<1	1400	2	<5	<20	27	0.03	<10	50	<10	<1	150
56	59806	330	0.8	1.44	150	85	<5	1.66	<1	89	21	228	3.50	<10	1.00	585	3	0.02	1	1480	10	<5	<20	33	<0.01	<10	48	<10	1	147
57	59807	30	<0.2	1.77	35	85	<5	1.29	<1	28	10	134	3.77	<10	1.23	850	2	0.03	<1	1630	8	<5	<20	25	0.02	<10	49	<10	<1	91
58	59808	50	<0.2	1.80	55	70	<5	2.82	<1	41	14	402	3.43	<10	1.28	840	3	0.02	2	1480	8	10	<20	48	0.05	<10	38	<10	4	74
59	59809	40	<0.2	1.74	40	95	<5	2.31	<1	25	11	83	3.54	<10	1.11	758	2	0.03	<1	1590	10	<5	<20	42	0.06	<10	48	<10	3	82
60	59810	45	<0.2	1.69	30	55	<5	2.33	<1	14	17	99	3.89	<10	1.13	718	11	0.04	1	1590	18	10	<20	40	0.08	<10	59	<10	2	43

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS-978

ECO-TECH LABORATORIES LTD.

Et.#	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Ni %	Ni	P	Pb	Sb	Sn	Br	Ti %	U	V	W	Y	Zn
61	59811	40	<0.2	1.80	70	85	<5	2.62	<1	13	28	175	4.20	<10	1.28	781	9	0.04	1	1550	14	<5	<20	43	0.08	<10	72	<10	2	51
62	59812	80	0.2	1.96	50	55	<5	2.46	<1	13	17	72	4.14	<10	1.42	849	7	0.04	1	1530	14	<5	<20	43	0.07	<10	70	<10	2	82
63	59813	110	0.8	1.77	35	60	<5	2.81	<1	17	13	121	3.89	<10	1.11	775	8	0.03	<1	1520	24	5	<20	51	0.08	<10	52	<10	3	89
64	59814	70	<0.2	1.26	35	75	<5	2.67	<1	21	13	208	3.34	<10	0.63	499	7	0.02	1	1580	14	<5	<20	52	0.08	<10	47	<10	4	155
65	59815	60	<0.2	0.89	25	100	<5	3.82	1	18	10	58	2.20	<10	0.48	509	<1	0.02	<1	1420	4	5	<20	68	0.04	<10	38	<10	3	109
66	59816	80	<0.2	0.88	85	50	<5	3.91	<1	24	9	53	2.77	<10	0.43	548	3	0.02	<1	1500	12	<5	<20	67	0.05	<10	27	<10	3	80
67	59817	170	<0.2	1.18	75	50	<5	3.14	<1	35	8	44	2.90	<10	0.71	568	<1	0.02	<1	1510	8	5	<20	30	0.05	<10	31	<10	3	55
68	59818	5	<0.2	2.00	30	85	<5	2.92	<1	11	15	87	3.88	<10	1.38	755	<1	0.03	<1	1480	<2	<5	<20	53	0.08	<10	51	<10	3	48
69	59819	5	<0.2	1.81	35	50	<5	3.01	<1	10	5	36	3.46	<10	1.28	867	<1	0.03	<1	1500	4	<5	<20	52	0.08	<10	41	<10	4	40
70	59820	10	<0.2	2.04	90	50	<5	2.79	<1	12	10	42	3.92	<10	1.48	891	<1	0.03	<1	1510	4	10	<20	51	0.07	<10	52	<10	3	53
71	59821	5	<0.2	1.88	40	125	<5	3.80	<1	13	8	83	3.88	<10	1.32	734	2	0.03	<1	1530	2	5	<20	78	0.08	<10	50	<10	4	52
72	59822	5	<0.2	1.94	70	75	<5	3.25	<1	16	8	83	4.34	<10	1.25	718	18	0.04	<1	1830	14	<5	<20	68	0.07	<10	57	<10	4	51
73	59823	10	<0.2	1.74	70	70	<5	4.53	<1	12	9	88	4.12	<10	1.18	785	3	0.03	1	1500	8	<5	<20	91	0.07	<10	51	<10	4	50
74	59824	5	<0.2	2.17	45	140	<5	3.57	<1	13	8	88	4.38	<10	1.55	733	1	0.03	<1	1580	14	<5	<20	78	0.08	<10	57	<10	2	78
75	59825	55	<0.2	1.71	130	85	<5	4.09	<1	26	11	188	4.48	<10	1.22	890	8	0.03	<1	1440	10	<5	<20	91	0.07	<10	49	<10	3	81
76	59826	80	<0.2	1.45	170	65	<5	2.78	<1	32	17	157	3.97	<10	0.98	728	18	0.03	<1	1110	48	<5	<20	75	0.08	<10	44	<10	3	99
77	59827	20	<0.2	1.28	205	90	<5	2.78	<1	48	20	170	3.82	<10	0.88	688	75	0.03	<1	930	80	<5	<20	74	0.08	<10	46	<10	4	85
78	59828	25	<0.2	1.40	200	50	<5	2.20	<1	45	18	185	4.30	<10	0.91	639	22	0.03	1	1010	18	<5	<20	57	0.07	<10	41	<10	4	110
79	59829	120	<0.2	1.58	695	80	<5	2.99	<1	91	21	142	4.35	<10	1.10	742	14	0.02	<1	980	30	<5	<20	87	0.07	<10	43	<10	3	122
80	59830	>1000	0.8	1.49	7025	75	<5	2.80	<1	502	24	284	5.55	<10	1.02	678	9	0.02	<1	1130	24	<5	<20	63	0.02	<10	49	<10	1	148
81	59831	385	0.4	1.83	2370	140	<5	2.09	<1	289	27	243	4.45	<10	1.19	799	3	0.01	<1	1070	22	<5	<20	46	0.05	<10	51	<10	2	213
82	59832	>1000	1.6	1.33	980	175	<5	1.85	<1	643	12	757	5.73	<10	0.91	477	12	0.01	<1	1190	8	<5	<20	50	0.08	<10	49	<10	<1	110
83	59833	790	0.4	1.73	200	280	<5	3.75	<1	139	13	220	3.73	<10	1.23	849	5	0.02	<1	1580	<2	10	<20	85	0.08	<10	44	<10	4	86
84	59834	205	<0.2	1.77	85	90	<5	3.13	<1	34	14	233	3.08	<10	1.32	741	2	0.02	<1	1470	<2	10	<20	89	0.08	<10	35	<10	3	48
85	59835	515	<0.2	1.83	85	80	<5	3.39	<1	57	9	201	3.70	<10	1.44	870	5	0.02	<1	1480	<2	5	<20	84	0.05	<10	39	<10	2	40
86	59836	35	<0.2	1.37	40	90	<5	2.79	<1	30	9	87	3.11	<10	1.02	540	3	0.03	<1	1470	2	5	<20	83	0.04	<10	38	<10	2	36
87	59837	>1000	<0.2	1.82	250	180	<5	1.87	1	209	10	284	4.96	<10	1.40	587	7	0.02	<1	1810	4	<5	<20	45	0.05	<10	65	<10	<1	188
88	59838	>1000	<0.2	1.84	150	225	<5	2.47	<1	118	22	122	3.84	<10	1.16	801	4	0.02	<1	1800	2	<5	<20	58	0.04	<10	43	<10	3	89
89	59839	>																												

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS- 976

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
96	59848	>1000	1.4	1.89	210	115	<5	0.40	<1	176	26	310	4.46	<10	1.16	552	4	0.01	<1	1470	10	<5	<20	10	<0.01	<10	53	<10	2	92
97	59847	155	0.4	2.19	350	135	<5	0.46	<1	614	18	423	5.72	<10	1.60	667	6	0.01	<1	1730	4	<5	<20	12	<0.01	<10	70	<10	<1	129
98	59848	>1000	2.8	2.37	380	120	<5	1.07	<1	817	7	1581	>10	<10	1.70	765	10	0.01	<1	1140	8	<5	<20	27	0.04	<10	96	<10	<1	134
99	59849	>1000	8.0	2.45	740	170	<5	0.45	<1	970	6	3768	>10	<10	1.73	737	16	0.01	<1	1110	8	<5	<20	14	0.03	<10	115	<10	<1	143
100	59850	370	<0.2	2.10	450	145	<5	0.66	<1	434	8	631	4.20	<10	1.48	546	2	0.01	<1	1670	4	<5	<20	17	0.03	<10	39	<10	2	112
101	59851	>1000	1.4	2.51	750	145	<5	0.80	<1	981	18	295	>10	<10	1.56	766	14	0.01	<1	940	8	<5	<20	25	0.04	<10	115	<10	<1	108
102	59852	>1000	0.6	2.05	75	80	<5	0.99	<1	93	11	157	4.33	<10	1.44	576	3	0.02	<1	1570	4	<5	<20	25	<0.01	<10	40	<10	<1	81
103	59853	>1000	1.0	1.68	115	105	<5	1.59	<1	56	10	600	4.70	<10	1.18	635	6	0.02	1	1310	6	<5	<20	36	0.01	<10	38	<10	<1	58
104	59854	805	<0.2	1.56	50	65	<5	3.05	<1	39	6	102	3.10	<10	1.16	735	2	0.03	<1	1500	6	5	<20	58	0.02	<10	32	<10	4	40

QC/DATA:

<i>Resplit:</i>																															
1	59751	>1000	1.0	2.08	20	110	10	2.04	5	43	18	47	7.71	<10	1.38	1498	6	0.01	1	1360	10	<5	<20	40	0.05	<10	91	<10	<1	1332	
36	59786	220	<0.2	2.11	355	76	<5	2.03	<1	282	22	64	4.82	<10	1.63	781	3	0.02	<1	1110	<2	<5	<20	51	0.06	<10	41	<10	2	96	
71	59821	10	<0.2	1.90	50	135	<5	3.60	<1	18	12	66	3.73	<10	1.32	734	2	0.04	<1	1560	4	<5	<20	73	0.06	<10	52	<10	4	54	

<i>Repeat:</i>																															
1	59751	>1000	1.0	2.03	20	105	5	2.06	5	41	14	47	7.48	<10	1.38	1496	5	0.01	<1	1340	8	<5	<20	40	0.05	<10	87	<10	<1	1301	
10	59760	5	<0.2	2.07	45	65	<5	2.39	<1	14	23	89	4.26	<10	1.45	901	5	0.05	<1	1600	24	<5	<20	44	0.08	<10	71	<10	3	84	
19	59769	5	<0.2	1.90	90	75	<5	3.39	<1	14	12	78	4.00	<10	1.12	746	13	0.05	<1	1550	20	<5	<20	63	0.07	<10	58	<10	4	48	
36	59786	175	<0.2	2.26	325	70	<5	2.08	<1	258	20	72	4.44	<10	1.57	748	2	0.02	<1	1060	<2	10	<20	52	0.06	<10	39	<10	2	91	
45	59795	45	<0.2	2.72	84	85	<5	1.64	<1	50	8	504	7.15	<10	2.32	621	6	0.03	4	1820	6	<5	<20	42	0.02	<10	134	<10	2	78	

54	59804	>1000	<0.2	1.54	20	125	10	1.40	2	38	19	42	4.65	<10	1.13	653	3	0.02	<1	1410	6	<5	<20	37	0.05	<10	55	<10	<1	918
71	59821	10	<0.2	1.72	45	110	5	3.42	<1	12	7	56	3.26	<10	1.24	719	2	0.03	<1	1420	4	<5	<20	67	0.04	<10	48	<10	3	45
80	59830	>1000	0.6	1.48	6800	80	<5	2.73	<1	484	24	262	5.42	<10	1.00	685	8	0.02	<1	1110	24	<5	<20	62	0.02	<10	48	<10	2	140
89	59839	>1000	0.2	2.22	115	85	<5	3.20	<1	87	14	375	5.05	<10	1.60	766	6	0.02	<1	1710	<2	<5	<20	81	0.06	<10	55	<10	3	96
96	59848	-	2.8	2.18	360	110	<5	1.03	<1	653	7	1470	>10	<10	1.60	721	9	0.01	<1	1040	4	<5	<20	27	0.03	<10	84	<10	<1	128

<i>Standard:</i>																															
GEO'97		150	1.2	1.70	65	150	<5	1.80	<1	19	64	77	4.04	<10	0.96	662	<1	0.03	24	650	18	<5	<20	59	0.11	<10	76	<10	6	74	
GEO'97		140	1.0	1.68	65	155	<5	1.86	<1	20	62	77	4.00	<10	0.98	661	<1	0.03	24	630	16	<5	<20	60	0.11	<10	75	<10	7	66	
GEO'97		155	0.8	1.76	70	156	<5	1.82	<1	18	66	73	3.95	<10	0.92	643	<1	0.02	22	620	16	5	<20	53	0.06	<10	74	<10	6	66	

dl/976
XLS/97Teuton

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AS 97-977

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

12-Sep-97

ATTENTION: DINO CREMONESE

No. of samples received: 129

Sample Type: Core

PROJECT #: Clone

SHIPMENT #: CL-4

P.O.#: Not given

Samples submitted by: Dale Roberts

ET #.	Tag #	Au (g/t)	Au (oz/t)	As (%)	Co (%)
1	59956	1.25	0.036	-	-
12	59967	1.81	0.053	-	-
13	59968	2.92	0.085	-	-
53	60008	2.32	0.068	-	-
77	60032	1.15	0.034	-	0.024
80	60035	-	-	-	0.020
99	60100	-	-	-	0.021
100	60101	11.73	0.342	1.23	0.209
101	60102	-	-	-	0.058
102	60103	3.02	0.088	-	0.041
104	60105	7.39	0.216	-	0.081
113	60114	30.70	0.895	1.32	0.153
115	60116	37.60	1.097	3.03	0.324

QC/DATA:

Standard:

STD-M	1.64	0.048	-	-
SUIA	-	-	-	0.041
Cd-1	-	-	0.66	-

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

XLS/97Teuton

12-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOOPS, B.C.
V2C 8T4

Phone: 604-573-5700
Fax: 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AS-977

TEUTON RESOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 129

Sample Type: Core

PROJECT #: Clone

SHIPMENT #: CL-4

P.O.#: Not given

Samples submitted by: Dale Roberts

Values in ppm unless otherwise reported

Et#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	59956	>1000	1.8	0.99	20	55	<5	2.57	<1	42	25	21	2.30	<10	0.70	572	4	0.02	<1	1810	8	15	<20	49	0.02	<10	25	<10	3	85
2	59957	5	<0.2	1.03	5	85	<5	2.42	<1	20	11	19	2.57	<10	0.71	633	<1	0.02	<1	1710	6	<5	<20	47	0.03	<10	31	<10	3	73
3	59958	10	0.2	1.13	<5	70	<5	2.81	<1	9	15	148	2.50	<10	0.88	718	<1	0.03	<1	1530	4	<5	<20	63	0.03	<10	31	<10	3	91
4	59959	5	<0.2	1.41	10	65	<5	2.85	<1	10	11	161	3.01	<10	1.13	736	2	0.03	<1	1830	8	10	<20	55	0.02	<10	34	<10	3	68
5	59960	5	<0.2	1.79	<5	95	<5	2.08	<1	6	11	29	3.22	<10	1.58	705	2	0.04	<1	1880	2	5	<20	47	0.02	<10	38	<10	2	74
6	59961	5	<0.2	1.83	10	90	5	2.71	<1	8	11	18	3.01	<10	1.42	684	3	0.04	<1	1860	<2	15	<20	55	0.02	<10	41	<10	3	97
7	59962	155	<0.2	1.58	20	135	<5	2.74	<1	9	13	63	3.23	<10	1.30	749	2	0.04	<1	1810	4	10	<20	57	0.02	<10	41	<10	2	153
8	59963	5	<0.2	1.58	15	95	<5	3.49	<1	7	10	31	3.48	<10	1.41	881	2	0.04	<1	1830	2	10	<20	77	0.03	<10	56	<10	3	99
9	59964	5	<0.2	1.83	15	75	<5	2.12	<1	9	11	27	3.36	<10	1.45	795	1	0.04	<1	1830	4	10	<20	60	0.02	<10	48	<10	2	109
10	59965	5	<0.2	1.55	<5	220	5	2.38	<1	8	9	14	3.33	<10	1.36	791	3	0.03	<1	1840	<2	15	<20	69	0.02	<10	43	<10	1	98
11	59966	5	<0.2	1.37	100	55	<5	2.23	<1	19	28	23	3.78	<10	1.13	788	4	0.04	<1	1830	30	<5	<20	57	0.02	<10	39	<10	<1	110
12	59967	>1000	0.8	1.08	110	145	<5	1.90	<1	141	35	84	2.91	20	0.81	578	3	0.02	<1	1860	84	<5	<20	50	0.02	<10	49	<10	2	205
13	59968	>1000	1.0	0.92	95	55	<5	1.03	2	111	27	50	2.17	<10	0.56	358	3	0.02	<1	1750	74	<5	<20	24	<0.01	<10	32	<10	2	175
14	59969	55	0.4	0.84	45	75	<5	2.40	7	48	42	84	2.02	20	0.56	480	3	0.02	<1	1580	28	5	<20	58	<0.01	<10	30	<10	3	110
15	59970	60	0.8	1.36	20	80	<5	2.70	<1	12	35	97	4.04	<10	0.93	671	2	0.04	<1	1650	10	<5	<20	58	0.02	<10	80	20	<1	98
16	59971	10	<0.2	1.09	<5	235	<5	2.47	<1	10	33	36	3.81	<10	0.71	695	3	0.03	<1	1580	2	<5	<20	76	0.02	<10	87	<10	1	85
17	59972	5	<0.2	0.78	40	55	<5	2.59	<1	11	38	304	2.62	<10	0.49	650	4	0.03	<1	1580	8	<5	<20	74	<0.01	<10	37	<10	1	67
18	59973	5	<0.2	1.18	10	80	<5	3.04	<1	8	24	205	3.17	<10	0.74	785	3	0.04	<1	1590	8	5	<20	72	0.01	<10	55	<10	2	78
19	59974	5	<0.2	1.14	<5	80	<5	1.96	<1	8	28	28	3.54	<10	0.79	835	3	0.03	<1	1710	4	<5	<20	47	0.02	<10	53	<10	1	99
20	59975	5	0.6	0.88	15	60	<5	1.21	2	8	21	55	2.97	<10	0.51	361	3	0.02	<1	1680	6	<5	<20	34	<0.01	<10	39	<10	1	150
21	59976	20	<0.2	1.23	20	55	5	1.79	<1	9	8	16	3.15	<10	0.76	415	2	0.01	<1	1710	8	<5	<20	39	0.01	<10	21	<10	3	156
22	59977	5	<0.2	1.80	35	50	<5	2.32	<1	7	10	71	4.30	<10	0.95	583	3	0.02	<1	1630	4	<5	<20	53	0.01	<10	26	<10	3	62
23	59978	5	<0.2	1.55	25	90	<5	4.60	<1	10	12	75	2.98	<10	0.95	800	1	0.02	<1	1810	20	5	<20	111	0.02	<10	28	<10	2	74
24	59979	5	<0.2	1.47	10	70	<5	3.33	<1	18	15	84	2.81	<10	0.92	844	7	0.03	<1	1840	26	10	<20	85	<0.01	<10	33	<10	<1	62
25	59980	5	<0.2	1.33	15	70	<5	3.44	<1	13	18	91	3.05	<10	0.92	847	3	0.05	<1	1860	18	10	<20	102	<0.01	<10	42	<10	1	39

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS-977

ECO-TECH LABORATORIES LTD.

Et#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	59981	10	<0.2	1.08	20	135	<5	4.55	<1	12	14	81	2.81	<10	0.78	841	2	0.03	<1	1580	14	<5	<20	168	0.01	<10	25	<10	2	30
27	59982	5	<0.2	1.39	10	155	<5	3.88	<1	12	13	48	2.89	<10	0.98	523	2	0.04	<1	1590	2	8	<20	122	<0.01	<10	29	<10	1	34
28	59983	5	<0.2	1.88	<5	105	5	4.25	<1	9	12	14	3.38	<10	1.20	807	3	0.04	<1	1580	4	10	<20	120	0.01	<10	33	10	<1	37
29	59984	25	<0.2	1.56	90	160	<5	5.15	<1	75	15	90	2.97	<10	1.03	717	2	0.03	<1	1570	12	<5	<20	138	<0.01	<10	29	40	2	80
30	59985	5	<0.2	1.85	10	70	<5	3.89	<1	12	10	38	3.44	<10	1.13	727	4	0.04	<1	1580	6	<5	<20	96	<0.01	<10	42	<10	<1	48
31	59986	10	<0.2	1.87	45	50	<5	3.37	<1	29	29	45	3.63	<10	1.30	714	4	0.04	<1	1570	8	10	<20	119	0.02	<10	44	<10	<1	57
32	59987	5	<0.2	1.85	30	60	<5	3.48	<1	12	21	87	3.83	<10	1.54	715	4	0.04	<1	1570	12	15	<20	78	0.01	<10	58	<10	<1	51
33	59988	5	0.2	1.71	15	75	<5	3.17	<1	12	22	85	3.60	<10	1.25	648	3	0.05	<1	1580	8	<5	<20	88	0.01	<10	53	<10	<1	61
34	59989	100	<0.2	2.07	15	90	<5	4.08	<1	14	17	70	3.68	<10	1.34	704	3	0.04	<1	1840	<2	5	<20	95	0.01	<10	42	<10	2	72
35	59990	5	<0.2	1.87	10	70	<5	3.80	<1	10	18	89	3.11	<10	1.08	585	3	0.04	<1	1800	4	10	<20	78	0.01	<10	38	<10	2	53
36	59991	15	<0.2	1.92	<5	75	<5	2.30	<1	11	17	75	3.98	<10	1.43	818	2	0.04	<1	1820	4	<5	<20	48	0.02	<10	58	<10	<1	61
37	59992	10	<0.2	1.72	15	55	<5	2.88	<1	10	17	82	3.70	<10	1.35	858	3	0.05	<1	1820	4	5	<20	50	0.03	<10	72	<10	<1	49
38	59993	55	<0.2	1.84	45	85	<5	2.18	<1	17	27	171	4.59	<10	1.39	848	4	0.05	<1	1570	8	<5	<20	50	0.02	<10	87	<10	<1	55
39	59994	340	2.8	2.07	80	70	<5	2.20	1	43	18	985	6.51	<10	1.45	721	8	0.03	1	1530	12	<5	<20	48	0.01	<10	86	<10	<1	89
40	59995	15	0.4	1.71	20	85	<5	2.44	<1	12	28	138	4.01	<10	1.35	838	3	0.08	<1	1590	8	<5	<20	48	0.01	<10	88	<10	<1	88
41	59996	10	<0.2	1.88	15	55	<5	4.10	<1	10	19	70	3.75	<10	1.53	906	3	0.07	<1	1530	8	5	<20	95	<0.01	<10	108	<10	<1	88

42	59997	10	0.2	2.08	25	65	3.46	<1	11	20	111	4.36	<10	1.87	875	4	0.05	<1	1490	8	5	<20	120	<0.01	<10	100	<10	<1	72
43	59998	40	1.0	1.70	35	55	4.38	1	12	14	464	3.81	<10	1.27	848	3	0.05	<1	1530	10	<5	<20	128	<0.01	<10	88	<10	1	69
44	59999	60	0.8	1.85	30	65	3.34	<1	13	17	176	4.21	<10	1.35	921	4	0.04	<1	1560	20	5	<20	72	0.01	<10	91	<10	2	75
45	60000	120	1.4	1.85	20	75	3.48	<1	9	16	385	4.15	<10	1.29	906	3	0.04	<1	1530	8	5	<20	77	0.01	<10	85	<10	<1	83
46	60001	55	<0.2	1.87	10	80	3.53	<1	8	19	110	3.58	<10	1.18	877	3	0.05	<1	1590	8	<5	<20	71	0.02	<10	89	<10	<1	63
47	60002	5	0.4	1.81	25	110	7.18	<1	14	8	117	3.42	<10	1.33	1365	2	0.03	<1	1480	8	5	<20	183	0.01	<10	57	<10	3	63
48	60003	5	0.2	1.85	20	60	8.52	<1	12	14	53	3.70	<10	1.38	1166	3	0.04	<1	1450	8	<5	<20	98	<0.01	<10	52	<10	<1	57
49	60004	5	<0.2	1.86	45	60	4.42	<1	19	15	60	4.14	<10	1.41	963	3	0.05	<1	1570	6	<5	<20	94	<0.01	<10	80	<10	<1	55
50	60005	15	0.4	2.07	50	50	3.78	1	18	12	81	4.58	<10	1.55	1145	4	0.03	<1	1570	34	<5	<20	111	<0.01	<10	57	<10	<1	129
51	60006	85	0.6	1.78	495	55	4.59	<1	29	15	155	5.04	<10	1.29	1382	7	0.03	<1	1540	10	10	<20	108	0.01	<10	79	10	<1	63
52	60007	70	1.0	1.97	100	60	5.92	2	12	10	128	5.21	<10	1.30	2107	7	0.02	<1	1470	48	<5	<20	110	0.01	<10	73	<10	<1	208
53	60008	>1000	8.4	4.47	840	75	5.18	13	78	17	1558	>10	<10	2.58	5099	21	0.01	6	1380	552	<5	<20	105	0.03	<10	194	<10	<1	1879
54	60009	5	0.2	4.12	50	60	8.25	<1	41	35	225	9.11	<10	3.78	3317	5	0.03	14	1850	8	<5	<20	184	0.08	<10	282	<10	<1	98
55	60010	10	<0.2	3.80	50	45	>10	<1	35	32	182	7.96	<10	3.74	2484	6	0.04	13	1560	<2	<5	<20	241	0.08	<10	284	<10	<1	73
56	60011	25	<0.2	3.03	55	40	>10	<1	34	29	184	7.29	<10	2.89	2255	4	0.03	12	1420	4	10	<20	256	0.05	<10	226	<10	<1	49
57	60012	10	<0.2	4.08	45	40	9.57	<1	33	35	130	8.28	<10	4.04	2101	5	0.03	14	1680	4	<5	<20	181	0.05	<10	284	30	<1	120
58	60013	5	<0.2	3.50	25	50	5.27	<1	30	10	188	7.75	<10	3.34	1527	13	0.03	1	1830	14	<5	<20	136	0.05	<10	221	<10	2	78
59	60014	5	1.6	3.18	55	45	7.70	7	31	4	199	7.57	<10	3.07	1714	16	0.03	3	1690	362	10	<20	202	0.03	<10	210	<10	1	521
60	60015	5	<0.2	3.35	45	50	6.76	<1	36	2	148	8.21	<10	3.17	1702	15	0.02	4	1730	6	<5	<20	155	0.05	<10	236	<10	<1	110

ETUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS- 977

ECO-TECH LABORATORIES LTD.

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
61	60016	5	<0.2	3.46	30	40	5	6.83	<1	32	4	101	7.38	<10	3.41	1658	8	0.03	3	1830	4	<5	<20	174	0.04	<10	251	<10	<1	129
62	60017	5	<0.2	3.98	30	50	5	5.91	<1	33	6	88	7.96	<10	3.72	1577	6	0.02	3	1890	6	5	<20	185	0.03	<10	224	<10	<1	138
63	60018	15	0.6	3.30	65	60	10	9.68	1	34	21	103	7.73	<10	2.40	1741	8	0.02	11	1740	24	<5	<20	232	0.01	<10	122	<10	2	160
64	60018	25	1.4	2.82	110	85	5	4.35	<1	33	25	137	8.12	<10	1.88	1018	11	0.01	4	1470	44	<5	<20	138	0.01	<10	71	10	<1	75
65	60020	5	<0.2	4.00	95	75	5	6.53	<1	37	34	119	9.00	<10	3.50	1403	9	0.03	12	1770	12	<5	<20	281	0.02	<10	181	<10	<1	78
66	60021	5	<0.2	4.51	65	35	5	9.24	<1	33	36	86	8.33	<10	4.30	1638	6	0.05	14	1810	<2	<5	<20	316	0.03	<10	281	<10	<1	49
67	60022	55	<0.2	4.46	1910	45	10	9.72	<1	58	28	91	8.41	<10	4.16	1819	8	0.05	10	1890	<2	<5	<20	322	0.03	<10	288	<10	<1	56
68	60023	10	<0.2	4.44	80	50	5	5.58	<1	38	12	199	9.58	<10	3.92	1192	7	0.05	8	2070	4	<5	<20	185	0.03	<10	277	<10	<1	51
69	60024	985	<0.2	4.43	260	60	5	8.64	<1	55	25	145	8.75	<10	3.89	1519	8	0.06	11	2060	<2	<5	<20	253	0.03	<10	294	<10	<1	78
70	60025	10	<0.2	4.60	50	55	5	8.84	<1	38	35	153	8.89	<10	3.82	1683	7	0.05	9	2050	20	<5	<20	217	0.03	<10	282	<10	<1	102
71	60026	30	<0.2	4.51	30	65	5	7.04	<1	34	15	152	8.93	<10	3.87	1761	6	0.04	7	2270	<2	<5	<20	276	0.02	<10	224	<10	<1	103
72	60027	35	<0.2	5.10	75	75	5	5.13	<1	40	19	204	9.19	<10	4.63	1515	5	0.04	6	2400	4	<5	<20	210	0.02	<10	240	20	<1	81
73	60028	30	<0.2	5.11	60	70	5	8.75	<1	61	28	236	>10	<10	4.32	1980	10	0.03	18	1580	16	<5	<20	274	0.03	<10	329	<10	<1	89
74	60029	10	<0.2	4.90	50	85	5	7.07	<1	35	7	98	9.44	<10	4.21	1683	8	0.08	7	2030	<2	<5	<20	262	0.02	<10	253	10	4	66
75	60030	165	<0.2	5.19	740	90	10	5.27	<1	77	15	77	9.58	<10	4.49	1478	9	0.04	2	2350	6	<5	<20	197	0.02	<10	225	20	<1	58
76	60031	5	<0.2	5.67	85	80	15	5.73	<1	39	19	69	>10	<10	5.38	1633	5	0.04	10	2140	12	<5	<20	225	0.02	<10	293	50	<1	69
77	60032	>1000	0.4	5.04	5800	75	5	7.73	<1	279	14	167	>10	<10	4.58	1682	9	0.04	10	1990	18	<5	<20	268	0.02	<10	281	20	<1	101
78	60033	55	<0.2	3.52	70	85	5	5.98	<1	34	11	88	7.18	<10	2.97	1267	6	0.04	4	1330	6	15	<20	256	<0.01	<10	147	30	2	74
79	60034	85	<0.2	2.50	210	115	5	4.37	<1	35	15	48	4.94	<10	1.88	810	7	0.03	<1	1190	6	10	<20	215	<0.01	<10	80	<10	<1	49
80	60035	675	<0.2	5.51	2390	65	10	5.80	<1	210	45	117	>10	<10	4.78	1637	11	0.03	10	2070	6	<5	<20	219	0.02	<10	241	10	<1	81
81	60036	5	0.2	1.68	30	160	5	1.41	<1	16	28	24	5.13	<10	1.21	1187	2	0.05	<1	1820	54	<5	<20	44	0.07	<10	69	<10	<1	139
82	60037	5	<0.2	1.28	20	80	10	1.83	<1	10	17	26	5.36	<10	0.97	996	3	0.05	<1	1770	12	<5	<20	49	0.06	<10	90	20	<1	72
83	60038	25	<0.2	1.21	15	85	5	1.10	<1	22	51	13	3.45	<10	0.78	702	3	0.04	<1	1680	12	<5	<20	83	0.06	<10	48	<10	<1	102
84	60039	75	<0.2	2.08	15	120	5	1.28	<1	41	31	38	5.87	<10	1.62	1073	4	0.03	<1	1730	10	10	<20	27	0.05	<10	97	<10	<1	118
85	60040	20	<0.2	1.79	15	135	5	0.88	<1	22	30	178	4.70	<10	1.35	984	3	0.04	<1	1740	10	10	<20	34	0.06	<10	83	<10	<1	83
86	60041	5	<0.2	1.76	10	90	10	1.44	<1	15	21	12	4.74	<10	1.36	978	2	0.04	<1	1800	10	10	<20	41	0.06	<10	65	10	<1	77
87	60042	5	<0.2	1.71	15	100	10	1.29	<1	12	19	31	4.91	<10	1.33	1079	2	0.04	<1	1750	12	<5	<20	32	0.06	<10	76	<10	<1	121
88	60043	5	<0.2	1.55	15	95	10	1.77	<1	14	22	11	4.33	<10	1.15	991	2	0.04	<1	1750	6	<5	<20	46	0.06	<10	67	<10	<1	121
89	60044	5	<0.2	1.39	35	75	10	1.82	<1	18	28	8	4.05																	

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - A5- 977

ECO-TECH LABORATORIES LTD.

Et.#	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ce %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Se	Sr	Ti %	U	V	W	Y	Zn
96	60051	25	<0.2	1.58	10	85	10	2.69	<1	14	18	8	4.57	<10	1.43	932	<1	0.05	<1	1760	8	<5	<20	55	0.07	<10	74	10	<1	55
97	60052	75	<0.2	1.46	10	80	10	3.25	<1	23	21	8	4.18	<10	1.33	871	3	0.04	<1	1730	8	10	<20	62	0.07	<10	74	<10	1	48
98	60053	85	<0.2	1.78	20	70	5	2.98	<1	24	11	12	4.02	<10	1.57	837	<1	0.03	<1	1710	8	5	<20	58	0.07	<10	58	<10	1	53
99	60100	30	<0.2	2.22	300	95	<5	1.82	<1	234	8	182	4.41	<10	1.40	591	3	0.02	<1	1790	8	5	<20	41	0.01	<10	38	<10	<1	78
100	60101	>1000	6.0	2.94	>10000	90	<5	1.39	<1	1753	8	3865	>10	<10	1.58	725	32	0.01	<1	1030	46	<5	<20	31	0.02	20	65	60	<1	158
101	60102	975	1.0	3.27	845	125	<5	2.76	<1	593	22	855	>10	<10	2.04	923	12	0.01	<1	1850	8	<5	<20	70	0.02	<10	79	<10	<1	114
102	60103	>1000	2.4	2.75	1265	90	<5	2.88	<1	425	9	1237	8.50	<10	1.57	810	9	0.01	<1	1690	14	<5	<20	75	0.01	<10	58	10	<1	97
103	60104	115	<0.2	2.79	325	120	<5	0.95	<1	64	19	90	7.00	<10	1.49	555	6	0.01	<1	1720	8	<5	<20	18	0.01	<10	52	<10	<1	86
104	60105	>1000	4.4	2.38	4780	90	<5	3.31	<1	794	20	1646	>10	<10	1.30	710	25	0.02	<1	1250	36	<5	<20	94	0.02	10	51	<10	<1	84
105	60106	350	0.6	2.21	180	85	<5	1.29	<1	50	13	166	5.51	<10	1.33	720	4	0.03	<1	1890	28	<5	<20	30	0.01	<10	44	<10	<1	100
106	60107	30	0.2	1.81	25	85	<5	3.74	<1	13	19	67	3.78	<10	1.24	977	2	0.07	<1	1720	12	<5	<20	94	0.01	<10	56	<10	<1	57
107	60108	10	<0.2	1.73	20	75	5	3.34	<1	10	14	46	3.48	<10	1.24	877	2	0.05	<1	1760	8	10	<20	77	<0.01	<10	52	<10	<1	72
108	60109	5	<0.2	1.98	55	80	<5	2.81	<1	13	20	39	3.87	<10	1.52	1272	3	0.06	<1	1770	12	5	<20	56	0.02	<10	75	20	<1	63
109	60110	10	<0.2	1.77	105	90	<5	3.53	<1	16	16	115	4.19	<10	1.19	876	2	0.06	<1	1740	14	<5	<20	69	0.01	<10	63	<10	<1	60
110	60111	65	<0.2	1.91	150	105	<5	2.47	<1	26	22	140	4.76	<10	1.27	865	4	0.06	<1	1750	14	<5	<20	48	0.02	<10	96	10	<1	69
111	60112	30	0.2	1.58	45	75	<5	3.76	<1	12	23	145	4.38	<10	1.16	841	2	0.04	<1	1690	12	<5	<20	59	0.02	<10	89	20	<1	54
112	60113	20	0.4	1.83	65	75	<5	2.82	<1	20	19	184	4.68	<10	0.98	707	7	0.04	<1	1710	24	<5	<20	61	0.01	<10	62	<10	<1	74
113	60114	>1000	19.0	1.14	>10000	75	<5	3.39	<1	1096	22	4658	>10	<10	0.38	740	16	0.01	<1	100	108	<5	<20	67	<0.01	40	125	30	<1	130
114	60115	470	1.8	2.00	1490	70	<5	2.35	<1	149	11	411	7.06	<10	1.14	860	12	0.02	<1	1710	26	<5	<20	36	<0.01	<10	70	<10	<1	204
115	60116	>1000	21.0	2.08	>10000	80	<5	4.11	<1	2182	31	3704	>10	<10	0.94	1308	19	0.01	<1	270	196	<5	<20	106	0.01	<10	144	<10	<1	321
116	60117	255	0.2	2.02	155	65	<5	3.55	<1	21	22	105	3.99	<10	1.31	892	8	0.04	<1	1540	8	5	<20	112	<0.01	<10	46	<10	2	61
117	60118	75	<0.2	2.22	180	85	<5	2.92	<1	17	27	30	4.57	<10	1.54	710	4	0.06	<1	1850	4	<5	<20	56	0.04	<10	73	<10	2	28
118	60119	5	<0.2	2.04	70	55	5	3.42	<1	14	14	25	4.29	<10	1.48	998	6	0.06	<1	1690	8	<5	<20	64	0.03	<10	66	<10	2	28
119	60120	15	0.4	2.10	70	75	<5	3.78	<1	15	23	73	4.55	<10	1.62	929	7	0.05	<1	1680	12	5	<20	87	0.01	<10	85	<10	1	54
120	60121	25	0.8	1.68	40	70	<5	3.46	<1	18	24	112	4.69	<10	1.38	866	21	0.04	<1	1740	16	5	<20	101	<0.01	<10	87	<10	1	61
121	60122	25	0.4	1.74	30	70	<5	4.23	<1	14	20	108	4.30	<10	1.28	1001	29	0.06	<1	1710	22	<5	<20	115	<0.01	<10	100	<10	1	63
122	60123	415	2.4	3.10	1025	75	<5	8.07	<1	80	7	724	8.53	<10	2.06	2101	12	0.02	2	2170	32	<5	<20	161	0.02	<10	153	20	<1	109
123	60124	110	0.8	4.58	65	65	5	7.42	<1	32	42	243	>10	<10	3.62	2445	9	0.02	9	1690	84	<5	<20	183	0.03	<10	273	20	<1	191
124	60125	5	<0.2	4.35	35	55	<5	5.27	<1	41	22	178	8.60	<10	4.44	1836	13	0.04	10	1920	4	10	<20	175	0.03	<10	288	30	<1	74
125	60126	15	<0.2	4.22	25	65	<5	4.40	<1	39	10	172	8.95	<10	4.30	1574	13	0.04	6	1640	8	<5	<20	135	0.04	<10	285	20	<1	66
126	60127	5	<0.2	4.31	25	65	<5	4.09	<1	27	5	195	9.56	<10	4.19	1437	11	0.03	2	1930	8	<5	<20	122	0.05	<10	281	10	<1	49
127	60128	40	<0.2	4.62	45	55	<5	3.27	<1	32	9	149	9.34	<10	4.81	1331	10	0.04	4	2090	14	<5	<20	112	0.05	<10	283	40	<1	41
128	60129	5	<0.2	4.32	50	60	5	4.84	<1	36	7	181	9.42	<10	3.99	1481	9	0.05	2	2020	18	<5	<20	113	0.04	<10	297	50	1	51
129	60130	15	<0.2	3.87	50	60	<5	6.25	<1	33	3	208	8.16	<10	3.49	1510	20	0.06	1	1680	4	<5	<20	187	0.03	<10	268	<10	2	65

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - A5- 977

ECO-TECH LABORATORIES LTD.

Et.#	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ce %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Se	Sr	Ti %	U	V	W	Y	Zn	
QC/DATA:																															
Repeat:																															
1	59956	>1000	2.0	0.99	20	55	5	2.51	<1	41	10	23	2.33	<10	0.70	561	2	0.02	<1	1570	10	5	<20	46	0.02	<10	25	<10	4	85	
38	59991	15	<0.2	1.99	<5	90	<5	2.32	<1	11	22	73	4.10	<10	1.43	630	3	0.05	<1	1720	8	<5	<20	49	0.03	<10	81	<10	<1	68	
71	60026	30	<0.2	4.51	35	85	<5	7.19	<1	38	17	149	9.21	<10	3.86	1796	8	0.04	9	2400	<2	5	<20	269	0.02	<10	225	20	<1	110	
106	60107	35	<0.2	1.85	35	85	<5	3.76	<1	13	13	64	3.78	<10	1.28	976	3	0.07	<1	1700	12	<5	<20	92	0.01	<10	58	<10	<1	56	
Repeat:																															
1	59956	>1000	2.0	0.97	25	40	10	2.51	<1	41	12	21	2.24	<10	0.69	560	2	0.02	<1	1630	8	10	<20	36	0.02	<10	24	20	4	90	
10	59965	5	<0.2	1.57	<5	230	5	2.38	<1	7	9	14	3.36	<10	1.37	790	2	0.03	<1	1810	<2	10	<20	71	0.02	<10	44	<10	1	98	
19	59974	5	<0.2	1.15	5	85	<5	1.96	<1	8	28	28	3.55	<10	0.80	630	3	0.03	<1	1680	2	<5	<20	48	0.02	<10	53	<10	<1	96	
36	59981	15	<0.2	1.88	<5	70	<5	2.30	<1	11	17	73	3.97	<10	1.40	816	3	0.04	<1	1660	8	10	<20	45	0.02	<10	56	10	<1	64	
45	80000	145	1.4	1.80	20	60	<5	3.53	<1	9	16	368	4.23	<10	1.30	919	4	0.03	<1	1570	10	<5	<20	76	<0.01	<10	84	<10	<1	68	

54	80009	5	0.4	4.18	45	55	<5	8.38	<1	41	35	228	9.26	<10	3.81	3388	6	0.03	15	1700	10	<5	<20	186	0.06	<10	284	<10	<1	100	
71	80026	30	<0.2	4.44	45	60	<5	7.06	<1	35	17	149	8.96	<10	3.80	1787	6	0.04	8	2340	8	<5	<20	268	0.02	<10	222	<10	<1	108	
80	80035	685	<0.2	5.41	2255	65	15	5.77	<1	205	48	114	>10	<10	4.67	1524	15	0.03	13	2150	10	10	<20	211	0.02	<10	237	40	<1	84	
88	80044	5	<0.2	1.38	25	85	10	1.62	<1	17	27	7	4.02	<10	1.02	930	2	0.05	<1	1750	8	<5	<20	46	0.06	<10	63	<10	<1	92	
106	80107	35	0.2	1.82	45	80	<5	3.78	<1	14	19	70	3.85	<10	1.26	991	3	0.06	<1	1740	14	5	<20	92	0.01	<10	57	<10	<1	58	
115	60116	>1000	21.2	2.07	>10000	75	<5	4.05	<1	2221	31	3741	>10	<10	0.93	1308	19	<0.01	<1	300	202	<5	<20	103	0.01	<10	144	<10	<1	328	
124	80125	15	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Standard:																															
GEO'97		150	1.4	1.58	60	155	<5	1.87	<1	18	57	80	3.83	<10	0.90	668	<1	0.02	20	860	18	<5	<20	51	0.08	<10	76	<10	4	70	
GEO'97		140	1.4	1.52	60	150	<5	1.89	<1	19	58	78	3.93	<10	0.89	682	<1	0.02	22	880	22	<5	<20	55	0.07	<10	74	<10	5	70	
GEO'97		145	1.2	1.74	70	180	<5	1.82	3	21	57	82	4.39	<10	0.98	724	<1	0.03	22	740	28	<5	<20	57	0.08	<10	79	<10	5	72	
GEO'97		145	1.0	1.77	75	185	<5	1.81	2	20	57	83	4.31	<10	0.98	718	6	0.03	24	700	22	<5	<20	60	0.07	<10	79	<10	4	78	

df/977
XLS/977auton

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AS 97-1014

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

22-Sep-97

ATTENTION: DINO CREMONESE

No. of samples received: 44

Sample Type: Rock

PROJECT #: Clone

SHIPMENT #: CI-10

Samples submitted by: Dale Roberts

ET #.	Tag #	Au (g/t)	Au (oz/t)
32	60462	1.60	0.047
33	60463	47.10	1.374
38	60468	2.67	0.078
40	60470	4.65	0.136

QC/DATA:

Standard:

STD-M	1.43	0.042
-------	------	-------

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

XLS/97Teuton

Fax to Dino Vancouver 604-682-3992

18-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AS- 97-1014

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 44
Sample Type: Rock
PROJECT #: Clone
SHIPMENT #: CA-10
Samples submitted by: Dale Roberts

Value in ppm unless otherwise reported

Et#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	60431	385	1.2	1.78	985	80	<5	3.35	<1	45	48	440	5.88	<10	1.43	808	12	0.03	7	1270	10	<5	<20	57	0.05	<10	128	<10	<1	60
2	60432	125	0.4	1.30	445	45	<5	5.25	<1	24	50	181	3.10	<10	1.01	803	15	0.04	8	1220	8	5	<20	89	0.03	<10	88	<10	3	32
3	60433	75	0.6	1.48	135	45	<5	3.15	<1	18	38	241	3.89	<10	1.23	530	12	0.03	8	1280	8	10	<20	47	0.03	<10	115	<10	<1	41
4	60434	45	<0.2	1.78	110	45	<5	3.55	<1	14	48	171	4.10	<10	1.42	587	17	0.04	5	1370	8	5	<20	98	0.05	<10	108	<10	<1	38
5	60435	50	0.4	1.49	390	55	<5	4.00	<1	22	44	178	3.84	<10	1.12	613	18	0.04	4	1300	8	5	<20	71	0.02	<10	104	<10	<1	35
6	60436	55	0.4	1.86	75	40	<5	2.88	<1	18	40	210	4.19	<10	1.48	519	16	0.04	6	1290	8	<5	<20	53	0.01	<10	113	<10	<1	43
7	60437	115	0.4	1.60	95	35	<5	>10	<1	13	25	138	3.25	<10	1.38	1297	11	0.03	3	1150	8	10	<20	293	0.01	<10	75	<10	13	46
8	60438	435	0.8	0.92	760	15	<5	>10	<1	54	10	99	2.21	<10	0.82	2422	8	0.02	1	580	2	10	<20	883	<0.01	<10	30	<10	33	81
9	60439	70	0.4	1.29	120	35	<5	7.35	<1	15	21	108	3.13	<10	0.98	847	7	0.03	3	1090	8	5	<20	207	0.01	<10	78	<10	8	51
10	60440	410	0.4	2.07	2510	55	<5	5.32	<1	89	48	125	4.80	<10	1.71	834	15	0.03	8	1380	12	10	<20	146	0.01	<10	130	<10	<1	59
11	60441	95	<0.2	1.79	180	35	<5	3.72	<1	13	34	44	3.90	<10	1.60	643	5	0.05	3	1210	8	10	<20	115	<0.01	<10	150	<10	<1	41
12	60442	50	<0.2	2.21	50	40	<5	3.49	<1	14	40	37	4.84	<10	2.07	738	3	0.05	6	1470	10	10	<20	87	0.03	<10	205	<10	<1	52
13	60443	295	<0.2	2.14	185	45	<5	2.78	<1	18	41	38	4.38	<10	2.14	687	2	0.06	7	1420	8	5	<20	71	0.05	<10	195	<10	<1	43
14	60444	85	<0.2	1.87	185	40	<5	2.86	<1	24	38	81	3.71	<10	2.00	887	3	0.05	5	1340	10	15	<20	89	0.04	<10	187	<10	<1	47
15	60445	675	0.6	2.14	335	35	<5	4.22	<1	20	37	92	4.84	<10	2.31	770	3	0.04	5	1350	18	5	<20	101	0.02	<10	177	<10	<1	44
16	60446	40	<0.2	2.01	75	35	<5	4.87	<1	17	42	90	4.22	<10	1.90	854	3	0.04	4	1370	8	<5	<20	137	0.02	<10	185	<10	1	40
17	60447	30	<0.2	3.86	40	50	<5	4.45	<1	39	15	220	8.85	<10	3.52	1150	4	0.04	6	2230	10	<5	<20	102	0.09	<10	279	<10	3	58
18	60448	40	<0.2	2.05	30	40	5	3.11	<1	15	40	85	4.85	<10	1.80	840	4	0.05	6	1480	8	<5	<20	70	0.03	<10	199	<10	<1	42
19	60449	55	<0.2	2.72	85	45	<5	3.73	<1	25	35	118	6.15	<10	2.80	823	6	0.05	9	1850	12	5	<20	97	0.02	<10	220	<10	<1	52
20	60450	50	<0.2	1.85	40	45	<5	4.28	<1	17	37	91	4.08	<10	1.84	643	6	0.04	7	1430	10	5	<20	105	0.01	<10	182	<10	<1	41
21	60451	30	<0.2	2.00	30	55	<5	3.79	<1	18	40	71	4.20	<10	1.93	846	4	0.05	6	1450	12	10	<20	84	0.05	<10	183	<10	2	46
22	60452	85	<0.2	1.75	35	45	<5	5.94	<1	12	45	80	3.70	<10	1.67	756	8	0.05	5	1380	10	10	<20	148	0.05	<10	175	<10	3	43
23	60453	35	<0.2	1.48	10	65	10	1.85	<1	8	17	34	3.50	<10	1.11	816	1	0.03	<1	1480	14	<5	<20	31	0.04	<10	54	<10	<1	175
24	60454	55	<0.2	1.63	15	100	<5	2.82	<1	12	19	47	3.68	<10	1.14	918	1	0.04	2	1870	18	<5	<20	58	0.08	<10	57	<10	2	188
25	60455	45	<0.2	1.53	10	120	<5	2.05	<1	22	22	29	3.41	<10	1.13	708	<1	0.03	<1	1840	38	<5	<20	38	0.08	<10	62	<10	3	110

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS- 97-1014

ECO-TECH LABORATORIES LTD.

Et#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	60456	25	<0.2	1.70	10	75	5	1.44	<1	20	23	23	3.45	<10	1.34	804	1	0.04	<1	1830	24	<5	<20	32	0.05	<10	70	<10	1	153
27	60457	95	1.0	1.58	20	105	<5	1.86	<1	20	19	331	3.62	<10	1.18	855	1	0.03	1	1850	22	10	<20	48	0.08	<10	63	<10	2	216
28	60458	55	<0.2	1.38	10	75	10	2.18	<1	14	28	13	3.34	<10	1.05	682	2	0.04	<1	1860	30	<5	<20	48	0.08	<10	60	<10	3	91
29	60459	95	<0.2	1.10	10	185	5	1.80	<1	12	19	10	3.00	<10	0.74	531	<1	0.03	<1	1880	24	<5	<20	39	0.08	<10	53	<10	3	55
30	60460	85	<0.2	1.16	10	80	5	2.12	<1	15	19	10	3.35	<10	0.84	835	1	0.03	<1	1890	14	<5	<20	36	0.08	<10	62	<10	2	55
31	60461	70	<0.2	1.38	10	80	5	1.83	<1	14	20	9	3.24	<10	0.97	842	<1	0.03	1	1850	12	10	<20	30	0.06	<10	61	<10	2	81
32	60462	>1000	0.4	1.85	15	80	<5	2.55	<1	16	23	80	3.88	<10	1.10	737	1	0.04	<1	1880	108	<5	<20	88	0.08	<10	67	<10	2	82
33	60463	>1000	2.2	1.81	100	185	<5	0.74	1	26	7	428	>10	<10	0.89	490	19	0.02	<1	1780	80	<5	<20	22	0.08	<10	151	<10	<1	228
34	60464	285	0.6	1.84	70	110	<5	1.28	2	41	27	2495	>10	<10	1.18	775	14	0.02	3	1310	58	<5	<20	28	0.07	<10	144	<10	<1	284
35	60465	215	0.8	2.58	80	85	<5	0.88	38	87	12	9132	>10	<10	1.84	749	8	0.02	11	1850	18	<5	<20	15	0.07	<10	122	<10	<1	332
36	60466	120	<0.2	3.15	100	75	<5	0.89	4	115	35	1144	>10	<10	2.83	880	7	0.01	16	1500	10	<5	<20	17	0.09	<10	121	<10	<1	488
37	60467	985	<0.2	1.44	150	80	<5	0.85	<1	70	54	1093	>10	<10	0.98	354	13	0.01	9	1440	14	<5	<20	17	0.09	<10	122	<10	<1	214
38	60468	>1000	<0.2	2.04	175	95	<5	0.73	<1	132	38	2184	>10	<10	1.41	498	18	0.01	19	1820	20	<5	<20	22	0.08	<10	186	<10	<1	338
39	60469	385	0.4	1.59	215	70	<5	0.88	<1	182	26	2793	>10	<10	1.16	398	14	0.01	15	1900	12	<5	<20	20	0.07	<10	143	<10	<1	237
40	60470	>1000	0.8	1.34	180	75	<5	0.80	1	124	31	1438	>10	<10	0.84	345	18	0.01	13	1820	38	<5	<20	29	0.08	<10	141	<10	<1	213
41	60471	200	<0.2	3.17	35	70	<5	0.88	1	71	31	858	>10	<10	2.82	1004	9	0.02	12	2250	16	<5	<20	22	0.09	<10	154	<10	<1	283

42	60472	100	<0.2	3.88	40	90	<5	3.50	2	79	35	308	8.54	<10	3.35	1817	2	0.02	17	1990	30	<5	<20	47	0.18	<10	178	<10	2	170
43	60473	40	<0.2	3.13	30	140	<5	5.37	<1	41	32	190	8.97	<10	3.08	1849	1	0.04	18	1840	18	<5	<20	68	0.22	<10	213	<10	4	74
44	60474	75	<0.2	2.46	30	150	<5	5.84	<1	41	28	223	8.51	<10	2.59	1598	<1	0.04	15	1570	8	<5	<20	64	0.20	<10	221	<10	3	81

QC/DATA:

Resplit:																															
1	60431	370	1.2	1.64	1075	45	<5	3.32	<1	51	42	417	5.81	<10	1.34	805	12	0.02	8	1370	12	<5	<20	47	0.05	<10	122	20	<1	58	
36	60466	85	<0.2	3.23	110	75	<5	0.70	5	119	36	1034	>10	<10	2.84	888	7	0.01	18	1580	12	<5	<20	15	0.08	<10	129	<10	<1	518	
Repeat:																															
1	60431	345	1.2	1.74	940	50	<5	3.21	<1	43	41	399	5.28	<10	1.35	562	12	0.03	8	1230	14	<5	<20	51	0.04	<10	113	<10	<1	58	
10	60440	380	0.4	2.05	2510	55	<5	5.24	<1	90	51	120	4.58	<10	1.89	829	15	0.03	8	1380	14	15	<20	142	0.01	<10	130	<10	<1	59	
19	60449	55	<0.2	2.87	75	45	<5	3.81	<1	26	37	121	8.46	<10	2.74	860	8	0.05	7	1720	14	<5	<20	89	0.03	<10	231	<10	<1	57	
36	60466	80	<0.2	3.49	105	80	<5	0.75	5	127	39	1217	>10	<10	2.82	949	7	0.01	12	1840	18	<5	<20	18	0.11	<10	128	<10	<1	482	
Standard:																															
GEO'97		155	1.2	1.88	70	150	<5	1.72	<1	19	56	80	4.13	<10	0.91	674	<1	0.03	24	860	24	<5	<20	55	0.11	<10	78	<10	5	73	
GEO'97		-	1.2	1.71	60	155	<5	1.73	5	22	57	80	4.32	<10	0.85	694	<5	0.03	20	860	22	<5	<20	58	0.04	<10	79	<10	4	72	

df/1014
XLS/97Teuton
Fax to Dino Vancouver 604-882-3992

ECO-TECH LABORATORIES LTD.
Frank J. Pazzotti, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AS 97-1015

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

23-Sep-97

ATTENTION: DINO CREMONESE

No. of samples received: 64

Sample Type: Core

PROJECT #: Clone

SHIPMENT #: CL-8

Samples submitted by: Dale Roberts

ET #.	Tag #	Au (g/t)	Au (oz/t)	Co (%)
61	60371	-	-	0.028
62	60372	12.84	0.374	0.069

QC/DATA:

Standard:

STD-M

Su1a

1.43 0.042

0.041

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

XLS/97Teuton

Fax to Dino Vancouver 604-682-3992

19-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax: 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK-97-1015

TEUTON RESOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V8C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 64
Sample Type: Core
PROJECT #: Clone
SHIPMENT #: CL-8
Samples submitted by: Dale Roberts

Values in ppm unless otherwise reported

Et.#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	60311	140	<0.2	1.64	185	100	<5	1.90	4	27	24	127	4.00	<10	1.09	676	18	0.03	19	1450	16	105	<20	47	<0.01	<10	59	<10	<1	73
2	60312	820	1.4	1.53	990	55	<5	5.30	<1	25	20	372	3.66	<10	1.00	910	8	0.02	<1	1270	14	<5	<20	86	<0.01	<10	42	10	<1	73
3	60313	20	<0.2	1.84	100	50	<5	3.51	<1	12	17	47	3.74	<10	1.02	721	3	0.04	<1	1600	20	<5	<20	74	<0.01	<10	47	10	<1	67
4	60314	5	<0.2	1.72	45	60	<5	3.27	<1	11	17	28	3.80	<10	1.14	827	3	0.04	<1	1800	12	5	<20	81	0.01	<10	54	<10	<1	48
5	60315	35	0.2	1.84	50	55	5	2.23	<1	12	19	21	4.55	<10	1.41	584	4	0.04	<1	1810	14	<5	<20	47	0.01	<10	62	<10	<1	31
6	60316	40	<0.2	1.92	30	65	5	1.63	<1	10	20	12	4.37	<10	1.41	578	5	0.05	<1	1810	16	<5	<20	35	0.01	<10	100	<10	<1	53
7	60317	40	<0.2	1.72	15	45	10	2.94	<1	10	14	8	3.96	<10	1.40	687	3	0.04	<1	1510	20	<5	<20	41	0.02	<10	80	<10	2	51
8	60318	20	<0.2	1.81	15	55	<5	3.81	<1	11	28	26	3.70	<10	1.37	733	2	0.04	<1	1580	20	<5	<20	61	0.03	<10	62	<10	3	50
9	60319	55	<0.2	1.85	25	45	<5	4.17	<1	10	9	37	3.29	<10	1.47	758	2	0.03	<1	1590	14	10	<20	84	0.03	<10	60	<10	3	43
10	60320	15	<0.2	1.91	30	50	5	4.78	<1	11	12	23	4.02	<10	1.85	1087	3	0.03	<1	1510	16	10	<20	79	0.02	<10	81	<10	3	57
11	60321	930	5.2	3.75	1130	70	<5	8.07	57	117	15	609	>10	<10	2.45	2352	10	0.01	9	1500	1272	<5	<20	87	0.03	<10	181	<10	<1	5085
12	60322	20	<0.2	4.13	30	50	10	7.34	<1	27	35	101	9.28	<10	3.15	2419	5	0.02	13	1910	24	<5	<20	108	0.05	<10	227	<10	<1	104
13	60323	20	0.4	4.45	35	45	5	7.10	2	32	44	102	8.83	<10	3.88	2586	9	0.02	16	1780	150	<5	<20	148	0.04	<10	248	<10	<1	242
14	60324	5	<0.2	3.71	15	35	<5	6.33	<1	31	47	91	7.88	<10	3.73	1909	7	0.03	13	1720	18	<5	<20	153	0.03	<10	253	<10	<1	94
15	60325	30	0.6	4.24	25	45	5	5.29	2	35	3	115	8.89	<10	4.01	1750	31	0.02	7	1820	72	5	<20	118	0.03	<10	292	<10	1	108
16	60326	5	0.6	3.78	20	40	<5	9.64	21	33	34	85	7.88	<10	3.61	2087	70	0.02	12	1630	218	<5	<20	200	0.05	<10	269	<10	3	374
17	60327	10	<0.2	3.61	25	40	<5	6.87	<1	35	46	87	7.55	<10	3.66	1753	8	0.02	15	1890	18	<5	<20	171	0.06	<10	256	<10	1	79
18	60328	15	<0.2	3.27	25	40	<5	5.55	<1	33	25	121	7.52	<10	3.22	1519	9	0.02	9	1700	18	<5	<20	132	0.03	<10	238	<10	<1	69
19	60329	30	<0.2	3.84	20	50	<5	5.05	<1	33	26	151	8.97	<10	3.63	1422	10	0.02	8	1700	20	<5	<20	104	0.05	<10	275	<10	<1	63
20	60330	10	<0.2	3.94	20	50	<5	4.12	<1	33	9	152	9.04	<10	3.53	1395	17	0.02	8	1860	26	<5	<20	101	0.03	<10	284	<10	<1	64
21	60331	60	<0.2	4.40	25	50	5	6.10	<1	29	17	93	9.21	<10	4.13	1752	10	0.02	12	1720	22	<5	<20	139	0.06	<10	294	<10	1	70
22	60332	60	0.8	1.56	20	80	<5	1.19	<1	19	18	781	4.66	<10	1.15	700	1	0.02	1	1160	14	<5	<20	23	0.09	<10	59	<10	3	63
23	60333	15	<0.2	1.86	20	70	10	0.72	<1	21	19	54	5.40	<10	1.47	779	3	0.02	<1	1120	16	<5	<20	15	0.08	<10	57	<10	<1	84
24	60334	255	<0.2	2.41	25	115	<5	1.62	1	48	29	410	6.77	<10	2.18	1182	2	0.02	5	1480	26	<5	<20	24	0.10	<10	109	<10	<1	87
25	60335	10	<0.2	3.94	40	325	<5	4.43	3	49	38	286	8.76	<10	4.12	1886	<1	0.03	12	1990	22	<5	<20	57	0.16	<10	240	<10	2	88

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1015

ECO-TECH LABORATORIES LTD.

Et.#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	60336	75	<0.2	3.25	30	180	<5	7.00	1	39	68	122	7.92	<10	3.52	1837	<1	0.03	15	1830	18	<5	<20	70	0.14	<10	239	<10	<1	74
27	60337	20	<0.2	3.16	30	95	15	6.77	<1	35	65	47	7.42	<10	3.48	1581	<1	0.02	15	1950	16	<5	<20	83	0.15	<10	183	<10	2	108
28	60338	10	<0.2	3.08	30	70	5	5.13	<1	35	50	56	8.83	<10	3.58	1527	<1	0.02	14	2090	16	<5	<20	67	0.15	<10	184	<10	3	90
29	60339	5	<0.2	2.53	30	40	<5	8.46	<1	38	115	89	5.85	<10	3.03	1680	<1	0.02	20	1880	12	15	<20	78	0.12	<10	151	<10	2	59
30	60340	55	<0.2	2.69	30	35	<5	8.59	1	43	63	212	7.20	<10	3.08	1647	<1	0.03	17	1860	18	5	<20	74	0.15	<10	193	<10	<1	65
31	60341	60	<0.2	2.12	25	30	<5	8.55	<1	31	24	104	6.14	<10	2.39	1411	1	0.02	11	1430	10	5	<20	65	0.11	<10	161	<10	<1	50
32	60342	20	<0.2	2.68	25	115	<5	8.38	<1	37	56	167	7.35	<10	2.96	1356	<1	0.04	16	1820	28	<5	<20	85	0.14	<10	228	<10	<1	61
33	60343	65	<0.2	2.41	15	85	<5	8.20	1	32	48	139	5.82	<10	2.78	1318	<1	0.03	13	1850	30	10	<20	65	0.11	<10	241	<10	<1	49
34	60344	30	<0.2	2.98	25	50	<5	4.62	<1	34	26	127	7.10	<10	3.49	1415	<1	0.03	13	1900	16	10	<20	69	0.18	<10	187	<10	1	53
35	60345	15	<0.2	2.71	20	40	<5	2.58	<1	33	30	139	6.05	<10	2.83	1207	<1	0.04	10	1880	18	15	<20	62	0.12	<10	180	<10	2	51
36	60346	20	<0.2	3.15	20	50	5	2.83	<1	37	41	109	7.08	<10	3.88	1445	<1	0.05	14	2150	18	<5	<20	62	0.14	<10	191	<10	1	75
37	60347	30	<0.2	2.08	20	75	<5	2.80	<1	27	26	87	4.89	<10	2.90	1045	<1	0.03	7	1820	12	10	<20	48	0.08	<10	130	<10	2	53
38	60348	20	<0.2	2.21	20	50	<5	1.86	<1	27	28	89	4.84	<10	2.81	1023	<1	0.03	9	1870	12	5	<20	39	0.08	<10	128	<10	2	71
39	60349	30	<0.2	2.51	25	40	<5	3.94	<1	28	33	88	5.70	<10	3.00	1175	<1	0.03	9	1830	12	5	<20	48	0.11	<10	167	<10	1	46
40	60350	15	<0.2	3.77	35	45	<5	5.49	<1	41	56	148	8.15	<10	4.10	1604	<1	0.03	15	2130	18	<5	<20	68	0.15	<10	249	<10	2	88
41	60351	10	<0.2	3.84	20	50	10	4.50	<1	37	19	89	6.72	<10	4.16	1227	<1	0.04	14	2040	20	<5	<20	85	0.19	<10	244	<10	3	52

42	60352	40	<0.2	2.83	35	40	<5	3.85	<1	29	27	97	8.56	<10	3.42	850	<1	0.02	10	1770	14	<5	<20	53	0.11	<10	179	<10	1	43
43	60353	20	<0.2	3.55	20	45	<5	5.44	<1	40	34	75	8.14	<10	3.80	1192	<1	0.03	14	1890	20	<5	<20	74	0.17	<10	218	<10	3	61
44	60354	35	<0.2	2.75	30	55	<5	4.30	<1	26	28	131	8.88	<10	2.76	935	1	0.02	7	2060	18	5	<20	80	0.10	<10	171	<10	2	42
45	60355	65	<0.2	2.74	20	90	<5	1.42	<1	35	3	348	8.74	<10	2.28	858	4	0.02	1	2550	16	<5	<20	90	0.08	<10	150	<10	<1	51
46	60356	45	<0.2	4.13	25	80	<5	4.87	<1	33	36	190	9.67	<10	4.00	1232	3	0.03	12	2200	20	<5	<20	76	0.12	<10	248	<10	2	50
47	60357	100	<0.2	2.53	10	100	<5	4.03	6	20	22	122	6.67	<10	2.34	806	22	0.02	27	1710	14	120	<20	58	0.03	<10	152	<10	<1	31
48	60358	195	<0.2	2.97	20	55	<5	4.90	<1	23	7	175	7.97	<10	2.85	902	3	0.02	5	2180	20	<5	<20	77	0.09	<10	176	20	<1	34
49	60359	90	<0.2	2.83	205	80	<5	7.76	<1	51	13	155	7.48	<10	2.43	1355	12	0.02	7	1720	30	<5	<20	137	0.08	<10	173	<10	3	74
50	60360	100	1.0	3.00	85	45	<5	5.12	8	38	14	247	8.01	<10	2.80	1155	36	0.03	39	1850	22	180	<20	73	0.05	<10	224	<10	<1	83
51	60361	45	<0.2	3.37	85	50	<5	4.80	<1	53	22	388	9.89	<10	2.95	1145	17	0.03	16	1830	38	<5	<20	88	0.15	<10	244	10	<1	74
52	60362	55	<0.2	3.55	140	75	<5	3.41	<1	38	20	255	9.01	<10	3.35	1241	5	0.03	15	1870	28	<5	<20	48	0.09	<10	263	20	3	83
53	60363	25	<0.2	3.43	90	105	<5	3.17	<1	40	19	275	8.76	<10	3.72	1325	3	0.03	18	1770	22	<5	<20	58	0.20	<10	220	<10	4	54
54	60364	60	<0.2	2.93	75	130	<5	2.35	<1	34	21	217	7.37	<10	3.28	1223	3	0.04	12	1880	18	5	<20	88	0.18	<10	175	<10	5	51
55	60365	75	<0.2	3.58	95	80	5	3.18	<1	40	23	131	7.93	<10	3.89	1280	6	0.03	13	1780	20	<5	<20	81	0.20	<10	188	<10	2	54
56	60368	50	<0.2	3.58	85	100	10	5.90	<1	37	28	151	8.82	<10	3.80	1384	2	0.03	14	1700	28	<5	<20	82	0.21	<10	207	<10	2	81
57	60367	20	<0.2	4.22	100	125	10	5.69	<1	50	20	150	9.26	<10	4.80	1577	1	0.04	13	1820	32	<5	<20	93	0.22	<10	198	10	1	81
58	60368	25	<0.2	3.69	105	110	10	3.85	<1	35	19	121	8.53	<10	3.84	1253	1	0.04	15	1830	26	<5	<20	104	0.23	<10	188	<10	<1	51
59	60389	415	<0.2	3.51	115	90	<5	7.15	<1	48	21	393	8.49	<10	3.58	1434	2	0.03	17	1720	28	<5	<20	148	0.18	<10	204	<10	<1	89
60	60370	180	<0.2	3.46	135	55	<5	5.92	<1	48	14	267	8.38	<10	3.14	1308	3	0.03	10	1800	28	<5	<20	87	0.16	<10	190	20	2	96

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1015

ECO-TECH LABORATORIES LTD.

Et.#	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca%	Gd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
61	60371	410	0.6	2.05	380	95	<5	2.87	<1	268	8	453	5.54	<10	1.44	848	6	0.02	<1	1740	18	<5	<20	54	0.01	<10	54	<10	<1	143	
62	60372	>1000	9.8	2.08	980	75	<5	2.84	<1	888	21	3208	>10	<10	1.35	927	14	0.01	<1	1130	28	<5	<20	59	0.02	<10	64	<10	<1	164	
63	60373	140	0.8	1.79	75	80	<5	2.48	<1	48	10	173	4.18	<10	1.21	633	4	0.02	<1	1790	28	5	<20	40	0.01	<10	42	<10	<1	108	
64	60374	75	0.4	1.55	50	85	<5	3.03	<1	27	15	152	3.88	<10	1.00	611	3	0.02	<1	1700	28	<5	<20	53	0.01	<10	43	<10	<1	73	
QC/QATA:																															
<i>Resplit:</i>																															
1	60311	205	<0.2	1.69	165	85	<5	1.91	<1	26	20	122	4.09	<10	1.10	687	3	0.04	<1	1570	18	<5	<20	37	<0.01	<10	60	<10	<1	76	
36	60346	40	<0.2	3.08	25	50	<5	2.68	<1	37	37	111	7.04	<10	3.82	1428	<1	0.04	13	2150	18	<5	<20	62	0.14	<10	189	<10	1	75	
<i>Repeat:</i>																															
1	60311	150	0.8	1.75	165	90	<5	1.94	<1	28	25	128	4.11	<10	1.13	700	2	0.03	1	1550	14	<5	<20	40	<0.01	<10	81	<10	<1	74	
10	60320	10	<0.2	2.01	40	55	<5	4.93	<1	12	12	23	4.20	<10	1.74	1110	2	0.03	<1	1580	18	5	<20	81	0.03	<10	98	<10	3	60	
19	60329	20	<0.2	3.76	20	50	<5	5.00	<1	33	27	149	8.88	<10	3.58	1408	11	0.02	9	1710	20	<5	<20	102	0.04	<10	272	<10	<1	84	
36	60346	35	<0.2	3.48	20	65	<5	2.84	<1	40	41	117	7.72	<10	4.05	1583	<1	0.08	16	2300	18	<5	<20	72	0.12	<10	204	<10	2	82	
45	60356	100	<0.2	2.88	15	90	<5	1.41	<1	34	2	338	8.85	<10	2.22	644	5	0.02	2	2510	20	<5	<20	30	0.08	<10	147	<10	<1	51	
54	60364	70	<0.2	2.88	70	125	<5	2.28	<1	35	19	216	6.88	<10	3.00	1135	4	0.03	12	1820	20	5	<20	81	0.17	<10	162	<10	4	48	
<i>Standard:</i>																															
GEO'87		130	1.4	1.65	80	150	<5	1.73	<1	20	58	74	4.11	<10	0.91	888	<1	0.03	25	680	20	<5	<20	53	0.10	<10	78	<10	4	70	
GEO'87		165	1.2	1.73	80	155	<5	1.80	<1	21	59	80	4.32	<10	0.95	710	<1	0.03	25	740	22	<5	<20	55	0.12	<10	79	<10	5	75	

dl/1014
XLS/97Teuton
Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AS 97-1016

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

23-Sep-97

ATTENTION: DINO CREMONESE

No. of samples received: 56

Sample Type: Core

PROJECT #: Clone

SHIPMENT #: CL - 7

P.O. #: Not Given

Samples submitted by: Dale Roberts

ET #.	Tag #	Au (g/t)	Au (oz/t)	Co (%)
35	60289	5.50	0.160	-
44	60298	1.22	0.036	-
46	60300	1.43	0.042	0.024
47	60301	3.65	0.106	0.051
49	60303	1.13	0.033	0.058

QC/DATA:

Repeat #:

35	60289	6.14	0.179	-
----	-------	------	-------	---

Standard:

STD-M	1.43	0.042	-
Sula	-	-	0.041

XLS/97Teuton
Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

19-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 804-573-5700
Fax : 804-573-4557

ICP CERTIFICATE OF ANALYSIS - AK 97 - 1016

TEUTON RESOURCES CORPORATION
508-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 56
Sample Type: Core
PROJECT #: Clone
SHIPMENT #: CL - 7
P.O.#: Not Given
Samples submitted by: Dale Roberts

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	80255	110	<0.2	1.42	10	65	<5	2.02	<1	24	21	12	3.30	<10	1.23	682	1	0.03	2	1330	6	10	<20	48	0.06	<10	52	<10	1	45
2	80256	45	<0.2	1.57	5	55	<5	2.79	<1	17	23	47	3.44	<10	1.39	707	<1	0.03	1	1400	6	10	<20	57	0.08	<10	53	<10	2	37
3	80257	40	<0.2	1.85	10	70	<5	3.18	<1	18	21	72	3.81	<10	1.31	693	1	0.04	1	1450	8	10	<20	99	0.08	<10	63	<10	1	42
4	80258	45	<0.2	1.42	10	65	<5	3.28	<1	17	18	14	2.94	<10	1.08	531	<1	0.04	<1	1510	8	5	<20	104	0.08	<10	63	<10	3	41
5	80259	75	<0.2	1.58	10	40	<5	3.58	<1	74	28	11	3.18	<10	1.38	595	<1	0.08	1	1500	8	5	<20	111	0.06	<10	82	20	3	41
6	80260	50	<0.2	1.47	10	65	<5	2.85	<1	9	23	28	3.37	<10	1.17	597	<1	0.05	2	1510	8	5	<20	81	0.09	<10	72	<10	2	29
7	80261	40	<0.2	1.67	10	65	<5	2.55	<1	8	24	8	3.24	<10	1.32	618	<1	0.04	2	1520	8	5	<20	81	0.08	<10	59	<10	2	30
8	80262	45	<0.2	1.57	10	65	<5	2.59	<1	8	21	93	3.35	<10	1.22	638	<1	0.04	1	1480	10	5	<20	70	0.08	<10	66	<10	2	30
9	80263	30	<0.2	1.64	10	75	<5	3.00	<1	8	22	13	3.78	<10	1.25	717	1	0.05	<1	1480	8	5	<20	77	0.07	<10	84	<10	2	40
10	80264	70	<0.2	1.48	10	60	<5	1.90	<1	7	15	43	3.35	<10	1.17	696	<1	0.03	1	1370	8	5	<20	40	0.05	<10	48	<10	<1	68
11	80285	50	<0.2	1.43	20	120	5	2.09	<1	11	22	8	3.30	<10	0.91	674	2	0.03	1	1490	8	5	<20	42	0.05	<10	44	<10	3	92
12	80266	55	<0.2	1.58	15	90	<5	1.47	<1	15	15	15	3.07	<10	1.18	695	<1	0.03	1	1520	8	5	<20	36	0.06	<10	45	<10	3	238
13	80267	20	<0.2	1.83	5	80	<5	0.80	2	7	17	15	2.26	<10	1.10	612	6	0.02	5	1510	8	45	<20	22	0.04	<10	35	<10	2	738
14	80268	20	<0.2	1.77	10	70	<5	1.15	<1	7	17	30	2.86	<10	1.27	738	<1	0.02	<1	1440	8	10	<20	24	0.06	<10	39	<10	2	520
15	80269	35	<0.2	1.92	5	120	<5	1.98	3	7	20	88	3.07	<10	1.45	770	6	0.04	6	1510	12	45	<20	57	0.08	<10	47	<10	3	217
16	80270	15	<0.2	1.85	<5	80	<5	1.68	3	6	14	50	3.18	<10	1.48	867	<1	0.03	<1	1450	12	15	<20	44	0.08	<10	48	<10	2	263
17	80271	65	<0.2	1.49	10	210	<5	2.09	<1	17	15	74	3.05	<10	1.20	693	<1	0.05	<1	1480	12	5	<20	56	0.07	<10	58	<10	3	233
18	80272	30	<0.2	1.72	10	100	<5	2.97	<1	11	16	28	3.36	<10	1.42	679	<1	0.04	1	1480	12	10	<20	55	0.08	<10	48	<10	3	211
19	80273	25	<0.2	1.88	<5	80	<5	1.98	<1	7	13	24	3.07	<10	1.49	577	<1	0.03	<1	1490	10	5	<20	43	0.07	<10	37	<10	3	171
20	80274	5	<0.2	1.67	10	90	<5	2.61	<1	9	21	30	3.32	<10	1.38	578	<1	0.05	<1	1500	10	<5	<20	64	0.08	<10	52	<10	5	65
21	80275	15	<0.2	1.77	15	130	<5	1.69	<1	8	18	77	3.27	<10	1.48	513	1	0.04	1	1490	10	10	<20	46	0.06	<10	49	10	4	31
22	80276	35	0.6	1.62	10	100	<5	0.84	2	12	15	47	2.88	<10	1.08	463	2	0.03	<1	1490	14	5	<20	20	0.02	<10	36	<10	2	101
23	80277	20	<0.2	1.86	5	275	<5	2.90	2	20	27	100	3.84	<10	1.37	1027	1	0.05	1	1840	20	<5	<20	66	0.08	<10	74	<10	5	216
24	80278	45	0.2	1.95	10	70	<5	1.94	6	10	19	184	3.90	<10	1.32	1135	<1	0.04	1	1810	70	5	<20	39	0.08	<10	58	<10	4	467
25	80279	25	<0.2	1.58	75	60	<5	2.89	2	11	20	47	3.68	<10	1.15	885	2	0.04	<1	1450	34	10	<20	54	0.06	<10	48	<10	3	117

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK 97 - 1016

ECO-TECH LABORATORIES LTD.

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
26	80280	35	<0.2	1.71	15	60	<5	3.28	1	12	19	33	3.11	<10	1.25	661	<1	0.04	2	1480	18	10	<20	53	0.06	<10	51	<10	7	108
27	80281	35	<0.2	1.95	15	75	<5	2.00	<1	7	15	17	3.40	<10	1.48	843	<1	0.03	<1	1510	10	<5	<20	48	0.07	<10	43	<10	5	99
28	80282	15	<0.2	1.76	10	105	10	1.94	<1	7	14	12	3.20	<10	1.39	818	<1	0.04	<1	1530	12	<5	<20	48	0.07	<10	47	<10	4	72
29	80283	10	<0.2	1.84	15	160	<5	2.90	2	8	17	83	3.35	<10	1.41	930	1	0.03	1	1490	18	10	<20	63	0.05	<10	46	<10	4	117
30	80284	20	<0.2	1.43	<5	385	<5	2.28	<1	5	17	73	3.33	<10	1.10	686	2	0.04	1	1450	8	<5	<20	65	0.05	<10	56	<10	4	77
31	80285	15	<0.2	1.70	<5	80	<5	1.75	<1	11	18	25	3.83	<10	1.34	792	2	0.05	<1	1540	16	<5	<20	46	0.05	<10	81	<10	3	61
32	80286	40	<0.2	1.57	15	150	<5	3.88	3	11	24	79	3.32	<10	1.05	795	2	0.04	2	1440	24	<5	<20	113	0.03	<10	52	<10	2	68
33	80287	235	<0.2	1.81	15	140	<5	2.72	<1	27	14	82	3.44	<10	1.27	695	2	0.03	<1	1480	10	<5	<20	67	0.04	<10	38	<10	4	47
34	80288	685	1.0	1.44	15	115	<5	3.30	2	23	25	142	3.03	<10	0.93	659	3	0.02	<1	1420	10	<5	<20	75	0.03	<10	36	<10	3	113
35	80289	>1000	1.4	1.38	10	120	<5	4.08	3	15	13	994	5.14	<10	0.83	822	5	0.02	<1	1330	14	<5	<20	136	0.02	<10	60	<10	<1	98
36	80290	35	0.2	1.37	5	80	<5	3.19	1	11	14	160	2.52	<10	0.82	627	2	0.03	1	1450	14	<5	<20	66	0.01	<10	32	<10	3	88
37	80291	10	<0.2	1.60	15	75	<5	2.84	<1	12	10	18	2.83	<10	1.15	810	1	0.03	<1	1390	8	5	<20	54	0.01	<10	30	<10	2	33
38	80292	55	<0.2	1.50	10	240	<5	3.02	<1	7	7	25	2.50	<10	1.09	842	2	0.02	<1	1340	10	10	<20	74	0.02	<10	28	<10	3	29
39	80293	15	<0.2	1.04	<5	125	<5	3.29	<1	8	18	40	2.34	<10	0.67	654	1	0.04	<1	1380	12	<5	<20	77	0.03	<10	38	<10	3	28
40	80294	20	<0.2	1.24	10	45	<5	3.39	<1	18	11	37	2.58	<10	0.93	641	1	0.03	<1	1380	8	5	<20	77	0.03	<10	37	<10	3	35

41	60295	110	0.4	1.39	15	80	<5	2.81	<1	23	10	61	3.10	<10	0.99	560	2	0.04	1	1470	8	10	<20	71	0.01	<10	42	<10	2	33
42	60296	235	<0.2	1.31	20	55	<5	4.23	<1	18	15	42	2.88	<10	0.94	680	2	0.04	<1	1370	4	10	<20	125	0.01	<10	41	<10	2	40
43	60297	590	<0.2	1.44	30	65	<5	3.26	<1	42	12	119	3.06	<10	1.02	596	2	0.02	<1	1390	8	5	<20	81	0.02	<10	38	<10	1	57
44	60298	>1000	0.4	1.48	70	70	<5	3.35	<1	85	13	262	3.33	<10	1.02	670	2	0.02	<1	1420	10	10	<20	94	0.02	<10	41	<10	<1	83
45	60299	380	0.4	1.57	60	95	<5	3.84	5	81	18	355	3.28	<10	0.91	840	3	0.02	<1	1410	10	<5	<20	123	0.02	<10	35	<10	<1	97
46	60300	>1000	1.2	2.18	300	95	<5	2.78	<1	236	18	393	5.83	<10	1.40	774	6	0.01	<1	1310	18	<5	<20	118	0.02	<10	44	<10	<1	117
47	60301	>1000	1.6	2.92	720	80	<5	4.48	<1	488	13	1034	7.80	<10	1.78	975	12	0.01	<1	1220	14	<5	<20	119	0.01	<10	49	<10	<1	147
48	60302	255	<0.2	1.93	170	80	<5	1.32	<1	114	11	292	4.39	<10	1.14	488	3	0.02	<1	1530	14	<5	<20	32	0.01	<10	41	<10	<1	120
49	60303	>1000	1.4	1.89	2200	80	<5	2.32	<1	447	12	1170	5.52	<10	1.03	520	5	0.01	<1	1120	10	<5	<20	82	<0.01	<10	38	<10	<1	80
50	60304	25	<0.2	1.43	75	55	<5	2.69	<1	11	11	32	3.10	<10	0.85	566	2	0.03	<1	1300	12	<5	<20	84	<0.01	<10	37	<10	<1	39
51	60305	5	<0.2	1.64	95	60	<5	2.79	<1	18	18	59	3.74	<10	1.12	681	4	0.03	2	1340	14	<5	<20	61	<0.01	<10	46	10	<1	82
52	60306	5	<0.2	2.07	50	80	<5	2.21	<1	19	12	35	4.01	<10	1.37	695	4	0.03	<1	1540	12	<5	<20	52	0.01	<10	48	<10	<1	70
53	60307	5	<0.2	1.59	40	50	<5	2.53	<1	22	19	80	3.16	<10	1.20	725	2	0.04	1	1440	12	5	<20	88	<0.01	<10	51	<10	<1	89
54	60308	35	<0.2	1.80	30	65	<5	2.99	<1	13	23	95	3.96	<10	1.38	799	3	0.06	1	1500	10	<5	<20	89	0.01	<10	100	<10	<1	61
55	60309	170	0.2	1.94	45	70	<5	2.73	<1	17	28	118	4.18	<10	1.53	749	4	0.06	2	1510	18	5	<20	59	0.01	<10	90	<10	<1	60
56	60310	130	0.2	1.59	60	55	<5	3.21	<1	12	17	90	3.72	<10	1.18	820	4	0.05	2	1510	12	5	<20	89	0.01	<10	99	<10	<1	57

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK 97 - 1016

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
QC/DATA:																															
<i>Repslit:</i>																															
1	60255	75	<0.2	1.49	15	70	<5	2.08	<1	26	22	14	3.38	<10	1.31	691	<1	0.04	2	1290	8	5	<20	49	0.08	<10	58	<10	3	48	
36	60290	60	<0.2	1.40	15	80	<5	3.25	1	11	11	153	2.58	<10	0.84	636	2	0.03	1	1520	16	5	<20	67	0.02	<10	32	<10	3	68	
<i>Repost:</i>																															
1	60255	100	<0.2	1.46	15	70	5	2.21	<1	26	24	12	3.39	<10	1.43	706	<1	0.04	<1	1320	10	10	<20	44	0.09	<10	53	<10	2	49	
10	60284	45	<0.2	1.52	10	65	<5	1.92	<1	7	15	43	3.41	<10	1.17	703	<1	0.03	<1	1400	8	<5	<20	42	0.06	<10	47	<10	1	89	
19	60273	30	<0.2	1.82	15	75	<5	1.98	<1	7	14	24	3.03	<10	1.45	569	<1	0.03	1	1470	10	10	<20	42	0.07	<10	36	<10	3	171	
36	60290	50	<0.2	1.39	15	80	<5	3.21	1	11	14	159	2.52	<10	0.83	628	2	0.03	<1	1470	16	5	<20	88	0.01	<10	32	<10	3	70	
45	60299	-	0.4	1.45	65	85	<5	3.55	3	59	15	341	3.14	<10	0.88	620	2	0.02	<1	1400	12	<5	<20	116	0.02	<10	32	<10	<1	88	
<i>Standard:</i>																															
GEO'97		130	1.2	1.90	55	160	<5	1.83	<1	20	61	88	4.25	<10	1.00	700	<1	0.03	23	670	22	<5	<20	67	0.13	<10	82	<10	6	68	
GEO'97		125	1.2	1.80	60	150	<5	1.75	<1	19	58	82	4.07	<10	0.95	667	<1	0.03	23	840	22	<5	<20	63	0.12	<10	79	<10	6	69	

ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

dfl/1005
 XLS/97Teuton
 Fax to Dino Vancouver 604-882-3992

22-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax: 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AX- 87-1017

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 15
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: CL-3
Samples submitted by: VIC VELJKOVIC

Values in ppm unless otherwise reported

Et#	Tag#	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca%	Gd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	V-97-15	35	1.8	1.44	70	110	5	1.26	5	15	33	56	5.56	<10	0.87	1283	10	0.02	7	1560	6	<5	<20	28	<0.01	<10	44	<10	4	441
2	V-97-16	55	1.0	1.96	85	125	15	0.87	<1	17	30	38	6.31	<10	1.21	1320	7	0.03	7	1620	14	<5	<20	13	0.01	<10	63	<10	6	89
3	V-97-17	35	1.6	2.28	80	140	<5	0.76	1	23	66	100	5.99	<10	1.75	1452	8	0.02	21	1350	12	<5	<20	23	<0.01	<10	94	<10	2	186
4	V-97-18	10	0.8	2.13	65	140	<5	0.57	3	23	47	51	5.59	<10	1.44	1081	5	0.02	20	1370	6	<5	<20	18	<0.01	<10	73	<10	<1	308
5	V-97-19	25	1.6	2.68	60	135	5	0.41	1	23	60	62	6.53	<10	2.05	1279	6	0.03	21	1280	8	<5	<20	16	<0.01	<10	140	<10	<1	175
6	V-97-20	30	1.2	2.31	40	165	<5	0.58	1	19	62	52	5.29	<10	1.74	1267	6	0.02	18	1300	8	<5	<20	21	<0.01	<10	77	<10	3	110
7	V-97-21	30	1.8	2.05	55	165	<5	0.80	1	17	52	52	5.06	<10	1.35	1419	7	0.01	15	1170	8	<5	<20	30	<0.01	<10	57	<10	4	136
8	V-97-22	170	12.0	0.61	2800	45	<5	1.44	30	17	54	708	8.48	<10	0.24	866	9	0.02	5	630	150	45	<20	40	<0.01	<10	11	<10	<1	2484
9	V-97-23	280	9.6	0.68	750	60	<5	0.50	22	21	62	276	7.30	<10	0.22	908	12	0.02	6	540	48	<5	<20	16	<0.01	<10	12	<10	<1	1845
10	V-97-24	165	4.8	0.70	195	55	<5	3.38	78	8	58	287	4.13	<10	0.34	1183	27	0.02	3	600	16	<5	<20	103	<0.01	<10	11	<10	<1	5770
11	V-97-25	245	4.8	0.80	620	55	<5	1.25	9	14	49	267	4.42	<10	0.25	722	10	0.02	4	720	22	<5	<20	41	<0.01	<10	13	<10	<1	853
12	V-97-26	85	2.0	1.84	175	115	<5	3.27	7	18	29	139	6.41	<10	1.13	2000	7	0.02	13	1800	12	<5	<20	132	<0.01	<10	82	<10	5	524
13	V-97-27	100	2.0	2.02	105	85	5	3.91	<1	30	61	129	8.13	<10	1.61	1520	9	0.03	22	2030	14	<5	<20	142	<0.01	<10	121	20	1	78
14	V-97-28	55	1.6	1.48	100	115	<5	1.84	3	16	72	73	4.81	<10	1.26	1560	6	0.02	20	1070	48	<5	<20	77	<0.01	<10	43	<10	5	303
15	V-97-29	30	1.4	0.74	95	140	<5	0.81	4	11	39	71	3.30	<10	0.22	1371	6	0.01	19	1070	48	<5	<20	26	<0.01	<10	20	<10	4	441
QC/DATA:																														
Repeat:																														
1	V-97-15	70	1.8	1.37	75	110	<5	1.21	4	15	38	53	5.41	<10	0.84	1245	10	0.02	7	1540	12	<5	<20	26	<0.01	<10	42	<10	4	422
Repeat:																														
1	V-97-15	50	1.8	1.47	80	130	<5	1.25	4	15	33	59	5.52	<10	0.86	1282	10	0.02	7	1570	10	<5	<20	26	<0.01	<10	44	<10	5	450
10	V-97-24	195	4.8	0.68	215	55	<5	3.40	79	8	58	294	4.16	<10	0.33	1196	29	0.02	3	610	18	<5	<20	102	<0.01	<10	11	<10	<1	5888
Standard:																														
GEO'87		185	1.4	1.72	60	160	<5	1.73	<1	19	59	81	4.09	<10	0.94	699	<1	0.03	22	660	20	<5	<20	63	0.11	<10	77	<10	5	72

dl/1009
XLS/87Teuton
Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.
Frank J. Pazzotti, A.Sc.T.
B.C. Certified Assayer

22-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK 97-1018

TEUTON RESOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V9C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 31
Sample Type: Rock
PROJECT #: Clone
SHIPMENT #: CL - 5
P.O.#: Not Given
Samples submitted by: Vic Velykovic

Values in ppm unless otherwise reported

Et.#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	V-97-30	45	0.8	2.83	20	215	<5	0.52	<1	19	63	56	5.67	<10	2.05	926	5	0.03	32	1280	10	<5	<20	20	<0.01	<10	84	<10	<1	87
2	V-97-31	45	1.2	4.08	25	280	5	0.40	1	18	28	56	7.12	<10	4.08	1190	7	0.03	15	1510	16	<5	<20	18	<0.01	<10	168	<10	<1	135
3	V-97-32	70	3.6	2.17	70	110	<5	0.18	<1	15	63	110	5.15	<10	1.70	587	6	0.03	49	1280	30	10	<20	5	<0.01	<10	88	<10	<1	82
4	V-97-33	75	3.4	1.86	55	135	<5	0.16	<1	9	86	63	4.30	<10	1.43	312	5	0.03	37	1140	24	10	<20	5	<0.01	<10	61	<10	<1	82
5	V-97-34	55	3.0	2.42	55	130	<5	0.19	<1	17	80	82	5.36	<10	2.01	1076	7	0.02	54	1270	22	10	<20	6	<0.01	<10	71	<10	<1	67
6	V-97-35	75	3.0	2.51	65	105	<5	0.16	<1	13	59	79	5.33	<10	2.05	478	7	0.08	26	1120	28	10	<20	6	<0.01	<10	92	<10	<1	63
7	V-97-36	45	2.8	2.64	90	95	<5	0.16	<1	17	56	77	5.88	<10	2.17	556	6	0.05	23	1120	30	<5	<20	5	<0.01	<10	99	<10	<1	71
8	V-97-37	35	1.2	2.63	50	125	5	0.25	<1	15	35	63	5.08	<10	2.27	655	5	0.06	14	1200	16	<5	<20	9	<0.01	<10	111	<10	<1	70
9	V-97-38	55	1.2	0.80	70	135	<5	0.71	2	9	74	74	4.17	<10	0.42	625	7	0.02	4	820	12	<5	<20	18	<0.01	<10	15	<10	1	167
10	V-97-39	65	1.8	1.00	290	135	<5	2.12	<1	15	37	124	4.65	<10	0.73	703	27	0.02	6	1530	18	<5	<20	80	<0.01	<10	23	<10	3	182
11	V-97-40	55	1.0	1.63	100	150	<5	0.58	<1	14	38	72	5.31	<10	0.85	713	10	0.01	13	1240	12	<5	<20	23	<0.01	<10	42	<10	<1	125
12	V-97-41	25	0.8	0.85	55	205	<5	1.27	<1	11	36	52	3.00	<10	0.29	1076	7	0.02	35	1050	8	<5	<20	29	<0.01	<10	16	<10	3	67
13	V-97-42	45	1.4	1.05	100	205	<5	1.32	<1	15	32	58	4.42	<10	0.39	1338	10	0.01	34	1380	14	<5	<20	32	<0.01	<10	27	<10	4	49
14	V-97-43	45	2.4	0.57	85	175	<5	0.33	<1	14	53	98	4.37	<10	0.08	513	15	0.01	48	1400	26	<5	<20	15	<0.01	<10	19	<10	3	157
15	V-97-44	20	1.4	1.06	60	175	<5	2.62	<1	14	27	68	4.53	<10	0.38	1438	9	0.01	30	1020	16	<5	<20	69	<0.01	<10	24	<10	3	74
16	V-97-45	65	5.6	1.37	120	145	<5	1.32	<1	17	44	1046	5.34	<10	0.59	787	28	0.01	39	1010	20	<5	<20	33	<0.01	<10	45	<10	1	83
17	V-97-46	15	0.8	1.97	45	135	<5	1.23	<1	14	27	93	4.57	<10	1.00	709	5	0.01	29	1070	8	<5	<20	31	<0.01	<10	30	<10	<1	85
18	V-97-47	30	1.0	1.53	65	145	<5	3.61	<1	15	44	81	3.92	<10	0.71	1704	6	0.01	38	1180	10	5	<20	67	<0.01	<10	33	<10	4	54
19	V-97-48	30	1.8	1.03	95	135	<5	4.02	<1	15	51	97	3.71	<10	0.33	2227	7	0.01	42	1160	14	<5	<20	99	<0.01	<10	24	20	5	61
20	V-97-49	35	1.4	2.01	60	170	<5	2.82	2	19	34	67	4.98	<10	0.93	1802	6	0.01	30	1120	12	<5	<20	77	<0.01	<10	48	<10	2	227
21	V-97-50	15	0.2	0.88	15	165	<5	1.98	<1	2	50	5	1.76	10	0.41	798	4	0.02	2	440	6	<5	<20	57	<0.01	<10	7	<10	2	44
22	V-97-51	20	0.2	0.94	10	155	<5	1.58	<1	5	51	6	1.84	20	0.41	711	5	0.02	5	480	10	<5	<20	27	<0.01	<10	8	<10	3	107
23	V-97-52	60	2.2	1.40	140	85	<5	3.39	22	20	41	140	4.62	<10	1.15	1083	5	0.01	100	610	344	10	<20	69	<0.01	<10	29	<10	<1	1947
24	V-97-53	30	1.2	1.33	50	115	<5	1.84	2	16	49	123	3.82	<10	0.88	897	6	0.01	83	670	36	<5	<20	31	<0.01	<10	31	<10	2	184
25	V-97-54	35	1.2	0.97	95	85	<5	3.21	4	19	61	111	4.36	<10	0.97	993	23	0.01	68	890	124	<5	<20	79	<0.01	<10	72	<10	2	448

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK 97-1018

ECO-TECH LABORATORIES LTD.

Et.#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	V-97-55	85	1.4	0.83	125	90	<5	5.32	<1	17	81	61	4.50	<10	0.67	1297	19	0.01	53	890	16	<5	<20	180	<0.01	<10	41	<10	6	32
27	V-97-56	65	1.2	1.88	55	120	<5	5.59	1	19	33	114	5.41	<10	1.82	1482	6	0.02	28	1560	10	<5	<20	152	<0.01	<10	80	<10	3	121
28	V-97-57	250	3.2	1.08	180	90	<5	4.09	1	28	87	105	5.51	<10	1.78	1589	9	0.01	35	1250	38	10	<20	124	<0.01	<10	47	<10	4	232
29	V-97-58	60	6.4	1.08	150	135	<5	0.51	3	20	71	83	4.14	<10	0.54	1034	8	0.01	12	890	124	<5	<20	16	<0.01	<10	23	<10	3	334
30	V-97-59	40	1.4	1.92	90	120	5	0.73	2	28	24	65	5.87	<10	1.04	788	6	0.01	16	1180	18	<5	<20	19	<0.01	<10	38	<10	3	209
31	V-97-60	30	1.2	1.64	80	95	<5	1.49	<1	28	17	52	8.10	<10	1.08	667	6	0.01	11	1300	12	<5	<20	40	<0.01	<10	44	<10	2	118

QC/DATA

Repeat:																															
R/S 1	V-97-30	30	0.8	2.53	25	175	<5	0.50	<1	19	45	51	5.41	<10	1.89	873	5	0.02	32	1250	16	<5	<20	16	<0.01	<10	75	<10	<1	87	
Repeat:																															
1	V-97-30	15	0.6	2.74	20	200	10	0.50	<1	19	60	57	5.67	<10	2.02	920	5	0.03	32	1290	16	<5	<20	17	<0.01	<10	82	<10	<1	86	
10	V-97-39	65	1.8	0.88	295	115	<5	2.20	<1	15	38	127	4.72	<10	0.73	718	27	0.02	8	1800	18	<5	<20	81	<0.01	<10	23	<10	4	185	
19	V-97-46	-	1.8	1.00	95	135	<5	4.08	<1	15	51	96	3.75	<10	0.34	2248	7	0.01	41	1190	14	<5	<20	100	<0.01	<10	24	<10	5	56	
28	V-97-57	180	3.8	1.25	190	100	5	4.39	2	30	75	113	6.01	<10	1.99	1709	9	0.01	36	1320	38	5	<20	135	<0.01	<10	53	<10	4	245	

Standard: GEO'97 135 1.2 1.76 55 140 <5 1.68 <1 17 60 70 3.97 <10 0.80 700 <1 0.02 22 610 20 <5 <20 60 0.08 <10 75 <10 4 74

df/1009
XLS/97Teuton
Fax to Dino Vancouver 604-682-3952

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

22-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK- 97-1017

TEUTON RESOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 15
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: CL-3
Samples submitted by: VIC VELJKOVIC

Values in ppm unless otherwise reported

El #	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	V-97-15	35	1.8	1.44	70	110	5	1.28	5	15	33	56	5.58	<10	0.87	1283	10	0.02	7	1580	8	<5	<20	28	<0.01	<10	44	<10	4	441
2	V-97-16	55	1.0	1.96	85	125	15	0.67	<1	17	30	36	6.31	<10	1.21	1320	7	0.03	7	1620	14	<5	<20	13	0.01	<10	63	<10	6	89
3	V-97-17	35	1.6	2.28	80	140	<5	0.76	1	23	66	100	5.99	<10	1.75	1452	8	0.02	21	1350	12	<5	<20	23	<0.01	<10	94	<10	2	186
4	V-97-18	10	0.8	2.13	65	140	<5	0.57	3	23	47	51	5.59	<10	1.44	1061	5	0.02	20	1370	8	<5	<20	18	<0.01	<10	73	<10	<1	308
5	V-97-19	25	1.6	2.86	80	135	5	0.41	1	23	80	62	6.53	<10	2.05	1279	6	0.03	21	1280	8	<5	<20	18	<0.01	<10	140	<10	<1	175
6	V-97-20	30	1.2	2.31	40	165	<5	0.58	1	19	62	52	5.29	<10	1.74	1287	6	0.02	18	1300	8	<5	<20	21	<0.01	<10	77	<10	3	110
7	V-97-21	30	1.8	2.05	55	165	<5	0.80	1	17	52	52	5.08	<10	1.35	1419	7	0.01	15	1170	8	<5	<20	30	<0.01	<10	57	<10	4	138
8	V-97-22	170	12.0	0.81	2800	45	<5	1.44	30	17	54	708	8.48	<10	0.24	868	9	0.02	5	830	150	45	<20	40	<0.01	<10	11	<10	<1	2494
9	V-97-23	280	8.8	0.66	750	60	<5	0.50	22	21	62	278	7.30	<10	0.22	908	12	0.02	6	540	48	<5	<20	18	<0.01	<10	12	<10	<1	1845
10	V-97-24	165	4.8	0.70	195	55	<5	3.38	78	8	58	297	4.13	<10	0.34	1193	27	0.02	3	800	16	<5	<20	103	<0.01	<10	11	<10	<1	5770
11	V-97-25	245	4.8	0.80	620	55	<5	1.25	9	14	49	267	4.42	<10	0.25	722	10	0.02	4	720	22	<5	<20	41	<0.01	<10	13	<10	<1	953
12	V-97-26	85	2.0	1.64	175	115	<5	3.27	7	18	29	139	6.41	<10	1.13	2000	7	0.02	13	1800	12	<5	<20	132	<0.01	<10	82	<10	5	524
13	V-97-27	100	2.0	2.02	105	85	5	3.91	<1	30	61	129	8.13	<10	1.61	1520	9	0.03	22	2030	14	<5	<20	142	<0.01	<10	121	20	1	76
14	V-97-28	55	1.6	1.46	100	115	<5	1.84	3	16	72	73	4.81	<10	1.26	1590	6	0.02	20	1070	48	<5	<20	77	<0.01	<10	43	<10	5	303
15	V-97-29	30	1.4	0.74	95	140	<5	0.61	4	11	39	71	3.30	<10	0.22	1371	6	0.01	19	1070	46	<5	<20	26	<0.01	<10	20	<10	4	441
QC/DATA:																														
Repeat:																														
1	V-97-15	70	1.6	1.37	75	110	<5	1.21	4	15	38	53	5.41	<10	0.84	1245	10	0.02	7	1540	12	<5	<20	28	<0.01	<10	42	<10	4	422
Repeat:																														
1	V-97-15	50	1.8	1.47	90	130	<5	1.25	4	15	33	59	5.52	<10	0.86	1262	10	0.02	7	1570	10	<5	<20	26	<0.01	<10	44	<10	5	450
10	V-97-24	195	4.8	0.88	215	55	<5	3.40	79	8	58	294	4.16	<10	0.33	1198	29	0.02	3	610	18	<5	<20	102	<0.01	<10	11	<10	<1	5888
Standard:																														
GEO'97		185	1.4	1.72	60	180	<5	1.73	<1	19	59	81	4.08	<10	0.94	689	<1	0.03	22	660	20	<5	<20	63	0.11	<10	77	<10	5	72

d#1009
XLS/97Teuton
Fax to Dino Vancouver 604-662-3992

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

22-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK 97-1018

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V8C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 31
Sample Type: Rock
PROJECT #: Clone
SHIPMENT #: CL - 5
P.O.#: Not Given
Samples submitted by: Vic Velykovic

Values in ppm unless otherwise reported

Et#	Tag#	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	V-97-30	45	0.6	2.83	20	215	<5	0.52	<1	19	63	56	5.67	<10	2.05	926	5	0.03	32	1280	10	<5	<20	20	<0.01	<10	84	<10	<1	87
2	V-97-31	45	1.2	4.08	25	280	5	0.40	1	18	28	58	7.12	<10	4.06	1180	7	0.03	15	1510	16	<5	<20	18	<0.01	<10	169	<10	<1	135
3	V-97-32	70	3.6	2.17	70	110	<5	0.18	<1	15	63	110	5.15	<10	1.70	587	6	0.03	49	1280	30	10	<20	5	<0.01	<10	88	<10	<1	82
4	V-97-33	75	3.4	1.88	55	135	<5	0.16	<1	9	68	63	4.30	<10	1.43	312	5	0.03	37	1140	24	10	<20	5	<0.01	<10	81	<10	<1	82
5	V-97-34	55	3.0	2.42	55	130	<5	0.19	<1	17	80	82	5.38	<10	2.01	1076	7	0.02	54	1270	22	10	<20	8	<0.01	<10	71	<10	<1	87
6	V-97-35	75	3.0	2.51	65	105	<5	0.16	<1	13	59	78	5.33	<10	2.05	478	7	0.06	28	1120	28	10	<20	6	<0.01	<10	92	<10	<1	63
7	V-97-36	45	2.8	2.84	90	95	<5	0.16	<1	17	58	77	5.88	<10	2.17	558	6	0.05	23	1120	30	<5	<20	5	<0.01	<10	99	<10	<1	71
8	V-97-37	35	1.2	2.63	50	125	5	0.25	<1	15	35	63	5.08	<10	2.27	855	5	0.06	14	1200	16	<5	<20	9	<0.01	<10	111	<10	<1	70
9	V-97-38	55	1.2	0.90	70	135	<5	0.71	2	9	74	74	4.17	<10	0.42	625	7	0.02	4	820	12	<5	<20	18	<0.01	<10	15	<10	1	187
10	V-97-39	65	1.8	1.00	290	135	<5	2.12	<1	15	37	124	4.65	<10	0.73	703	27	0.02	6	1530	16	<5	<20	80	<0.01	<10	23	<10	3	182
11	V-97-40	55	1.0	1.83	100	150	<5	0.58	<1	14	38	72	5.31	<10	0.85	713	10	0.01	13	1240	12	<5	<20	23	<0.01	<10	42	<10	<1	125
12	V-97-41	25	0.8	0.85	55	205	<5	1.27	<1	11	38	52	3.00	<10	0.29	1078	7	0.02	35	1050	8	<5	<20	28	<0.01	<10	18	<10	3	87
13	V-97-42	45	1.4	1.05	100	205	<5	1.32	<1	15	32	58	4.42	<10	0.39	1338	10	0.01	34	1380	14	<5	<20	32	<0.01	<10	27	<10	4	49
14	V-97-43	45	2.4	0.57	85	175	<5	0.33	<1	14	53	88	4.37	<10	0.08	513	15	0.01	48	1400	26	<5	<20	15	<0.01	<10	19	<10	3	157
15	V-97-44	20	1.4	1.06	80	175	<5	2.62	<1	14	27	86	4.53	<10	0.38	1438	9	0.01	30	1020	16	<5	<20	69	<0.01	<10	24	<10	3	74
16	V-97-45	65	5.6	1.37	120	145	<5	1.32	<1	17	44	1046	5.34	<10	0.58	787	28	0.01	39	1010	20	<5	<20	33	<0.01	<10	45	<10	1	83
17	V-97-46	15	0.8	1.97	45	135	<5	1.23	<1	14	27	93	4.57	<10	1.00	708	5	0.01	29	1070	8	<5	<20	31	<0.01	<10	30	<10	<1	85
18	V-97-47	30	1.0	1.53	65	145	<5	3.81	<1	15	44	81	3.82	<10	0.71	1704	6	0.01	36	1180	10	5	<20	87	<0.01	<10	33	<10	4	54
19	V-97-48	30	1.6	1.03	95	135	<5	4.02	<1	15	51	97	3.71	<10	0.33	2227	7	0.01	42	1160	14	<5	<20	99	<0.01	<10	24	20	5	61
20	V-97-49	35	1.4	2.01	60	170	<5	2.92	2	19	34	87	4.98	<10	0.93	1802	6	0.01	30	1120	12	<5	<20	77	<0.01	<10	48	<10	2	227
21	V-97-50	15	0.2	0.88	15	165	<5	1.98	<1	2	50	5	1.76	10	0.41	798	4	0.02	2	440	6	<5	<20	57	<0.01	<10	7	<10	2	44
22	V-97-51	20	0.2	0.94	10	155	<5	1.56	<1	5	51	6	1.84	20	0.41	711	5	0.02	5	480	10	<5	<20	27	<0.01	<10	8	<10	3	107
23	V-97-52	60	2.2	1.40	140	85	<5	3.39	22	20	41	140	4.82	<10	1.15	1063	5	0.01	100	610	344	10	<20	89	<0.01	<10	28	<10	<1	1947
24	V-97-53	30	1.2	1.33	50	115	<5	1.64	2	16	49	123	3.82	<10	0.88	897	6	0.01	83	670	38	<5	<20	31	<0.01	<10	31	<10	2	184
25	V-97-54	35	1.2	0.97	95	85	<5	3.21	4	18	81	111	4.38	<10	0.97	993	23	0.01	68	890	124	<5	<20	79	<0.01	<10	72	<10	2	448

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK 97-1018

ECO-TECH LABORATORIES LTD.

Et#	Tag#	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
26	V-97-55	95	1.4	0.83	125	90	<5	5.32	<1	17	81	61	4.50	<10	0.67	1297	18	0.01	53	890	16	<5	<20	180	<0.01	<10	41	<10	6	32
27	V-97-56	65	1.2	1.68	55	120	<5	5.58	1	19	33	114	5.41	<10	1.92	1482	6	0.02	28	1560	10	<5	<20	152	<0.01	<10	80	<10	3	121
28	V-97-57	250	3.2	1.08	180	90	<5	4.09	1	28	87	105	5.51	<10	1.79	1588	9	0.01	35	1250	38	10	<20	124	<0.01	<10	47	<10	4	232
29	V-97-58	60	6.4	1.06	150	135	<5	0.51	3	20	71	63	4.14	<10	0.54	1034	8	0.01	12	890	124	<5	<20	16	<0.01	<10	23	<10	3	334
30	V-97-59	40	1.4	1.92	90	120	5	0.73	2	28	24	65	5.97	<10	1.04	788	6	0.01	16	1180	18	<5	<20	19	<0.01	<10	38	<10	3	208
31	V-97-60	30	1.2	1.64	80	95	<5	1.49	<1	28	17	52	6.10	<10	1.08	867	6	0.01	11	1300	12	<5	<20	40	<0.01	<10	44	<10	2	118

QC/DATA

Repeat:																															
R/S 1	V-97-30	30	0.6	2.53	25	175	<5	0.50	<1	19	45	51	5.41	<10	1.89	873	5	0.02	32	1250	18	<5	<20	16	<0.01	<10	75	<10	<1	87	
Repeat:																															
1	V-97-30	15	0.6	2.74	20	200	10	0.50	<1	19	60	57	5.67	<10	2.02	920	5	0.03	32	1290	16	<5	<20	17	<0.01	<10	82	<10	<1	88	
10	V-97-38	65	1.8	0.88	295	115	<5	2.20	<1	15	38	127	4.72	<10	0.73	718	27	0.02	6	1800	18	<5	<20	81	<0.01	<10	23	<10	4	185	
19	V-97-48	-	1.8	1.00	95	135	<5	4.08	<1	15	51	86	3.75	<10	0.34	2248	7	0.01	41	1190	14	<5	<20	100	<0.01	<10	24	<10	5	56	
28	V-97-57	180	3.8	1.25	180	100	5	4.38	2	30	75	113	6.01	<10	1.88	1708	9	0.01	38	1320	38	5	<20	135	<0.01	<10	53	<10	4	245	

Standard:
GEOB7

135	1.2	1.76	55	140	<5	1.68	<1	17	60	70	3.97	<10	0.80	700	<1	0.02	22	610	20	<5	<20	80	0.09	<10	75	<10	4	74
-----	-----	------	----	-----	----	------	----	----	----	----	------	-----	------	-----	----	------	----	-----	----	----	-----	----	------	-----	----	-----	---	----

df/1009
XLS/97Teuton
Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.
Frank J. Pazzotti, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AS 97-1020

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

22-Sep-97

ATTENTION: DINO CREMONESE

No. of samples received: 56

Sample Type: Core

PROJECT #: Clone

SHIPMENT #: CL - 9

P.O.#: Not Given

Samples submitted by: Dale Roberts

ET #.	Tag #	Au (g/t)	Au (oz/t)
56	60430	1.40	0.041

QC/DATA:

Standard:

STD-M 1.43 0.042

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

XLS/97Teuton

Fax to Dino Vancouver 604-682-3992

22-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 8T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK- 97 1020

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 56
Sample Type: Core
PROJECT #: Clone
SHIPMENT #: CL - 9
P.O.#: Not Given
Samples submitted by: Dale Roberts

Values in ppm unless otherwise reported

Et #	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	60375	225	1.0	1.82	230	65	<5	2.51	<1	32	25	191	3.55	<10	1.22	831	5	0.02	4	1370	18	5	<20	59	0.01	<10	35	<10	<1	78
2	60376	75	0.2	2.13	85	70	<5	2.34	<1	13	34	155	4.53	<10	1.88	802	9	0.05	4	1500	8	10	<20	80	0.01	<10	83	<10	<1	125
3	60377	55	0.8	2.19	100	60	<5	3.11	<1	18	50	390	4.99	<10	1.57	894	12	0.05	4	1040	12	<5	<20	74	0.01	<10	79	<10	1	108
4	60378	5	0.4	2.19	70	55	<5	3.70	<1	18	35	340	4.81	<10	1.83	875	7	0.04	3	950	10	<5	<20	82	0.01	<10	86	<10	2	112
5	60379	55	<0.2	1.94	25	45	<5	5.24	2	13	30	77	4.01	<10	1.49	1131	3	0.04	3	1100	12	<5	<20	129	0.04	<10	102	<10	7	188
6	60380	45	0.4	2.19	25	80	<5	4.24	<1	13	40	378	4.43	<10	1.78	1000	13	0.05	1	1100	12	5	<20	112	0.04	<10	110	<10	8	160
7	60381	220	<0.2	1.74	25	45	<5	4.50	2	10	34	182	3.40	<10	1.40	853	11	0.05	3	1310	8	5	<20	113	0.04	<10	87	<10	5	114
8	60382	55	<0.2	2.10	45	60	<5	3.65	<1	12	32	108	4.14	<10	1.70	793	13	0.06	2	1520	12	<5	<20	82	0.06	<10	79	<10	6	74
9	60383	30	<0.2	2.14	25	75	<5	1.89	<1	11	25	79	4.21	<10	1.78	894	9	0.05	3	1580	10	10	<20	49	0.02	<10	78	<10	3	64
10	60384	15	<0.2	2.08	15	60	<5	2.12	<1	11	24	78	4.12	<10	1.72	877	8	0.05	2	1510	8	<5	<20	39	0.04	<10	77	<20	4	51
11	60385	5	<0.2	2.38	20	55	<5	2.60	<1	13	23	83	4.46	<10	1.95	755	8	0.06	2	1840	10	<5	<20	58	0.04	<10	81	10	4	52
12	60386	45	<0.2	2.03	20	55	<5	2.17	<1	14	22	88	4.29	<10	1.81	877	6	0.04	3	1390	8	<5	<20	44	0.02	<10	70	<10	2	54
13	60387	15	0.2	2.09	50	90	<5	2.23	<1	14	24	115	4.27	<10	1.51	881	4	0.05	2	1480	10	5	<20	57	0.01	<10	76	<10	2	74
14	60388	30	<0.2	2.11	40	75	<5	3.49	<1	14	28	80	4.13	<10	1.52	856	4	0.05	2	1390	8	<5	<20	64	0.01	<10	67	<10	4	60
15	60389	35	<0.2	2.01	15	80	<5	3.42	<1	14	35	95	4.21	<10	1.38	810	9	0.05	4	1450	10	<5	<20	61	0.02	<10	65	<10	3	58
16	60390	35	<0.2	1.63	20	60	<5	4.19	<1	14	24	109	3.58	<10	1.00	787	11	0.05	3	1470	8	<5	<20	76	0.05	<10	48	<10	8	48
17	60391	20	<0.2	1.91	30	85	<5	3.13	<1	15	26	122	4.08	<10	1.28	778	8	0.05	3	1500	18	<5	<20	57	0.03	<10	65	<10	2	58
18	60392	10	<0.2	1.95	10	50	<5	3.99	<1	18	28	178	4.11	<10	1.45	788	17	0.05	2	1380	12	<5	<20	75	0.04	<10	61	<10	4	44
19	60393	5	<0.2	2.01	15	50	<5	2.43	<1	14	28	131	4.29	<10	1.53	876	16	0.05	3	1540	10	<5	<20	51	0.02	<10	61	<10	2	40
20	60394	50	<0.2	2.15	15	60	<5	2.93	<1	13	25	100	4.20	<10	1.58	785	26	0.05	4	1600	12	5	<20	55	0.02	<10	63	20	2	45
21	60395	15	<0.2	2.37	15	80	<5	2.43	<1	14	24	97	4.83	<10	1.78	834	8	0.06	3	1620	10	<5	<20	48	0.02	<10	78	<10	1	56
22	60396	10	<0.2	1.83	25	50	<5	2.91	<1	12	21	103	3.90	<10	1.30	799	13	0.05	2	1450	10	<5	<20	61	0.01	<10	81	<10	1	54
23	60397	10	<0.2	1.88	45	60	<5	3.78	<1	10	38	38	3.91	<10	1.23	902	5	0.05	3	1130	10	<5	<20	94	<0.01	<10	82	30	3	63
24	60398	30	<0.2	2.08	50	65	<5	2.89	<1	15	30	76	4.83	10	1.33	842	3	0.04	2	1170	10	<5	<20	88	<0.01	<10	82	<10	2	76
25	60399	40	0.4	2.25	70	90	<5	2.25	<1	17	31	134	4.84	<10	1.45	868	5	0.04	3	1400	12	<5	<20	52	<0.01	<10	88	<10	2	77

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK- 97 1020

ECO-TECH LABORATORIES LTD.

Et.#	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	60400	30	0.2	1.98	25	60	<5	4.03	<1	14	25	138	4.14	<10	1.38	830	11	0.05	2	1480	10	5	<20	87	0.02	<10	79	10	3	60
27	60401	30	<0.2	2.12	30	50	<5	2.98	<1	13	47	98	4.37	<10	1.55	834	49	0.08	3	1550	10	<5	<20	73	0.02	<10	81	<10	2	53
28	60402	35	0.2	1.90	35	45	<5	3.10	<1	13	33	98	4.50	<10	1.40	839	23	0.05	3	1230	10	<5	<20	81	0.01	<10	98	<10	2	80
29	60403	80	<0.2	1.92	80	55	<5	2.64	<1	17	30	94	4.44	<10	1.34	732	10	0.04	3	1310	10	<5	<20	74	0.02	<10	89	<10	<1	58
30	60404	10	<0.2	2.04	30	45	<5	2.81	<1	13	27	78	4.42	<10	1.49	829	11	0.05	2	1320	10	<5	<20	73	0.02	<10	88	<10	2	73
31	60405	60	0.2	1.94	95	55	<5	3.88	<1	14	32	128	4.47	<10	1.38	860	5	0.04	3	1090	22	<5	<20	86	0.03	<10	108	<10	3	82
32	60406	38	<0.2	1.90	20	45	<5	3.97	<1	14	28	81	4.31	<10	1.34	887	11	0.04	3	1240	10	<5	<20	74	0.04	<10	84	<10	4	84
33	60407	165	<0.2	2.02	70	60	<5	4.85	<1	12	39	127	4.17	<10	1.38	992	10	0.04	3	1280	10	<5	<20	96	0.02	<10	61	<10	3	51
34	60408	45	<0.2	1.72	20	55	<5	3.25	<1	14	21	99	4.07	<10	1.17	727	7	0.04	3	1550	8	<5	<20	73	0.05	<10	55	<10	4	42
35	60409	15	<0.2	1.74	5	50	<5	4.11	<1	13	32	93	4.14	<10	1.22	855	9	0.05	3	1500	8	<5	<20	84	0.03	<10	88	10	4	38
36	60410	55	<0.2	1.99	15	60	<5	3.07	<1	11	24	111	4.37	<10	1.41	754	8	0.05	3	1530	22	<5	<20	80	0.03	<10	73	<10	2	71
37	60411	30	<0.2	1.78	15	55	<5	2.97	1	15	24	142	4.17	<10	1.22	887	10	0.07	3	1570	14	<5	<20	83	0.05	<10	75	<10	3	57
38	60412	70	<0.2	1.89	30	55	<5	3.24	<1	15	32	184	5.02	<10	1.30	750	21	0.08	3	1510	12	<5	<20	74	0.03	<10	90	<10	1	61
39	60413	50	<0.2	1.88	55	60	<5	3.98	<1	16	21	194	5.00	<10	1.23	925	22	0.05	2	1500	12	<5	<20	81	<0.01	<10	83	<10	2	59
40	60414	110	<0.2	1.82	35	50	<5	2.81	<1	14	23	139	4.43	<10	1.29	739	18	0.08	3	1580	14	<5	<20	58	<0.01	<10	77	<10	2	87
41	60415	95	<0.2	1.88	20	50	<5	3.32	<1	12	23	112	4.07	<10	1.32	825	11	0.05	2	1550	12	10	<20	70	<0.01	<10	87	10	2	48

42	60418	60	<0.2	1.92	25	60	<5	3.86	<1	14	25	131	4.21	<10	1.34	984	11	0.04	3	1390	18	<5	<20	65	0.01	<10	78	<10	<1	83
43	60417	180	<0.2	4.48	70	60	<5	5.85	<1	27	38	232	>10	<10	3.44	1771	8	0.02	12	1750	28	<5	<20	217	0.07	<10	240	<10	<1	113
44	60418	925	2.4	4.81	175	90	<5	3.78	5	80	58	1080	>10	<10	3.81	1782	13	0.02	10	1770	128	<5	<20	89	0.06	<10	268	<10	<1	475
45	60419	100	<0.2	5.30	40	60	<5	5.85	6	20	78	150	>10	<10	4.24	2784	8	0.01	14	1680	132	<5	<20	129	0.08	<10	272	<10	<1	339
46	60420	95	<0.2	4.46	80	55	<5	4.40	<1	35	41	109	8.59	<10	4.44	1319	3	0.02	13	2110	40	5	<20	134	0.11	<10	287	<10	<1	86
47	60421	35	<0.2	3.64	35	50	<5	5.38	<1	30	14	86	7.58	<10	3.08	1372	3	0.03	4	2380	18	<5	<20	122	0.08	<10	230	<10	3	74
48	60422	35	<0.2	4.63	30	55	<5	5.90	<1	27	24	73	9.38	<10	4.36	1850	4	0.02	13	1810	18	<5	<20	145	0.08	<10	278	<10	<1	75
49	60423	55	<0.2	4.05	15	80	<5	4.74	<1	28	28	134	9.43	<10	3.38	1426	5	0.02	13	2120	20	<5	<20	118	0.05	<10	260	10	<1	89
50	60424	40	<0.2	3.30	25	45	5	>10	<1	23	36	106	7.37	<10	2.76	1808	4	0.02	11	1730	18	<5	<20	203	0.08	<10	214	<10	4	78
51	60425	45	<0.2	2.36	15	40	<5	5.13	<1	25	7	170	6.12	<10	2.03	1051	3	0.03	2	2190	16	<5	<20	108	0.06	<10	158	<10	<1	54
52	60426	165	0.4	1.98	655	55	<5	3.67	<1	52	17	193	5.58	<10	1.47	885	12	0.04	3	1800	28	<5	<20	71	0.03	<10	129	<10	1	72
53	60427	90	<0.2	2.03	430	35	<5	3.58	<1	23	33	60	3.81	<10	2.00	654	13	0.03	7	1330	14	10	<20	55	0.08	<10	121	<10	2	53
54	60428	590	0.2	2.37	180	55	<5	4.78	<1	55	38	158	5.08	<10	1.94	934	8	0.04	8	1530	20	5	<20	88	0.09	<10	117	10	3	78
55	60429	155	<0.2	2.02	2745	45	<5	4.98	<1	77	38	118	4.45	<10	1.85	752	16	0.04	8	1470	18	15	<20	74	0.05	<10	145	10	1	57
56	60430	>1000	1.4	2.28	5405	50	<5	4.71	<1	83	38	228	5.38	<10	2.00	775	14	0.03	9	1420	26	10	<20	82	0.04	<10	125	<10	<1	58

TEUTON RESOURCES CORPORATION ICP CERTIFICATE OF ANALYSIS - AK- 97 1020 ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn	
QC/DATA:																															
<i>Repeat:</i>																															
R/S 1	60375	185	1.0	2.05	300	85	<5	2.77	<1	38	27	202	3.82	<10	1.35	898	6	0.02	2	1560	20	<5	<20	85	0.01	<10	38	<10	<1	84	
R/S 36	60410	40	<0.2	1.87	25	50	<5	3.02	<1	12	33	111	4.38	<10	1.38	743	7	0.05	3	1800	24	<5	<20	74	0.03	<10	71	<10	2	82	
<i>Repeat:</i>																															
1	60375	230	1.0	1.88	230	60	<5	2.55	<1	33	25	195	3.82	<10	1.25	843	5	0.02	2	1430	22	10	<20	58	0.01	<10	36	<10	<1	78	
10	60384	5	<0.2	2.25	15	65	<5	2.27	<1	12	27	79	4.44	<10	1.87	728	8	0.08	3	1800	10	<5	<20	43	0.05	<10	84	<10	4	54	
19	60393	10	<0.2	2.07	10	55	<5	2.50	<1	15	25	134	4.42	<10	1.58	897	16	0.05	2	1590	10	<5	<20	52	0.02	<10	83	30	2	42	
36	60410	65	<0.2	2.04	20	60	<5	3.19	<1	13	24	113	4.58	<10	1.43	782	7	0.05	3	1650	24	<5	<20	78	0.03	<10	78	<10	3	87	
45	60419	100	<0.2	5.17	50	55	5	5.69	5	20	77	147	>10	<10	4.09	2753	9	0.01	13	1740	136	<5	<20	128	0.08	<10	284	<10	<1	348	
<i>Standard:</i>																															
GEO'97		155	1.0	1.80	65	155	<5	1.76	2	19	59	85	4.14	<10	0.97	891	5	0.03	23	880	20	35	<20	82	0.08	<10	79	<10	5	75	
GEO'97		140	1.0	1.79	70	155	<5	1.78	<1	20	62	82	4.23	<10	0.98	893	<1	0.03	24	880	22	<5	<20	82	0.12	<10	80	10	5	72	

ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

df/1020
 XLS/87Teuton
 Fax to Dino Vancouver 604-682-3992

22-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AS- 97-1025

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 35
Sample Type: CORE
PROJECT #: CLONE
SHIPMENT #: CL-5
Samples submitted by: DALE ROBERTS

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	60054	80	<0.2	1.11	10	75	<5	2.84	<1	30	34	23	3.05	<10	0.98	577	<1	0.04	3	1640	28	5	<20	59	0.07	<10	57	<10	2	64
2	60055	85	<0.2	1.40	15	45	5	2.95	<1	52	24	13	3.29	<10	1.29	617	<1	0.06	4	1790	20	10	<20	83	0.07	<10	65	<10	2	80
3	60056	5	<0.2	1.59	10	65	<5	1.99	<1	10	25	18	3.68	<10	1.37	585	1	0.04	2	1720	16	10	<20	56	0.07	<10	80	<10	<1	42
4	60057	30	<0.2	1.79	10	65	<5	1.98	<1	9	15	10	3.68	<10	1.56	614	<1	0.03	3	1670	14	15	<20	53	0.07	<10	48	<10	<1	39
5	60058	25	<0.2	1.77	10	65	10	2.57	<1	9	22	11	3.70	<10	1.46	662	1	0.04	4	1710	14	15	<20	64	0.07	<10	53	<10	1	37
6	60059	15	<0.2	1.69	15	80	<5	2.35	<1	10	16	65	3.70	<10	1.30	638	<1	0.03	2	1720	14	10	<20	62	0.07	<10	55	<10	1	43
7	60060	75	0.4	1.72	25	105	<5	1.73	<1	9	15	74	3.47	<10	1.37	731	2	0.03	2	1650	12	10	<20	42	0.05	<10	39	<10	1	62
8	60068	15	<0.2	1.82	10	85	<5	1.44	<1	27	9	26	2.99	<10	1.46	786	<1	0.02	2	1710	14	10	<20	26	0.05	<10	38	<10	3	604
9	60069	5	<0.2	1.21	5	95	<5	2.64	<1	10	30	151	3.30	<10	0.90	588	<1	0.05	3	1820	12	5	<20	60	0.07	<10	63	<10	4	149
10	60070	10	<0.2	1.78	10	175	5	1.27	<1	8	12	15	3.51	<10	1.55	588	<1	0.03	2	1720	12	5	<20	33	0.06	<10	37	<10	2	142
11	60071	30	<0.2	1.82	15	75	10	1.36	<1	7	19	20	3.55	<10	1.38	500	2	0.04	2	1720	14	10	<20	36	0.04	<10	48	<10	3	78
12	60072	5	<0.2	1.40	<5	80	<5	2.54	<1	8	16	48	3.73	<10	1.31	502	<1	0.04	1	1810	18	5	<20	67	0.07	<10	59	<10	2	41
13	60073	40	<0.2	1.56	5	70	10	2.47	<1	8	15	27	3.90	<10	1.39	538	1	0.05	3	1690	12	5	<20	62	0.05	<10	60	20	3	37
14	60074	55	0.4	1.12	25	50	<5	2.59	<1	5	18	11	2.99	<10	0.89	441	2	0.03	2	1520	10	15	<20	82	0.01	<10	34	<10	2	39
15	60138	20	<0.2	1.07	10	65	10	1.01	<1	16	21	12	3.51	<10	0.76	667	1	0.03	4	1710	10	5	<20	24	0.05	<10	52	<10	1	149
16	60139	50	<0.2	1.58	10	115	10	1.04	<1	19	23	20	4.83	<10	1.25	987	1	0.03	2	1700	16	5	<20	29	0.07	<10	68	<10	<1	218
17	60140	125	<0.2	1.21	40	135	10	1.52	<1	22	19	34	4.40	<10	0.90	768	2	0.02	3	1610	22	5	<20	31	0.06	<10	66	<10	1	113
18	60141	30	<0.2	0.85	15	80	5	2.21	1	13	21	9	3.30	<10	0.57	722	2	0.03	3	1600	16	<5	<20	36	0.05	<10	48	<10	2	70
19	60142	15	0.2	1.03	15	70	<5	2.30	<1	10	24	42	3.36	<10	0.78	786	1	0.04	2	1570	16	10	<20	47	0.05	<10	58	<10	2	76
20	60143	15	0.2	1.35	10	90	<5	1.90	<1	12	26	160	3.65	<10	0.89	809	<1	0.04	2	1730	18	<5	<20	52	0.06	<10	71	<10	1	59
21	60144	20	<0.2	1.19	10	90	10	1.92	<1	14	21	12	3.83	<10	0.82	736	<1	0.03	3	1770	14	10	<20	49	0.07	<10	55	<10	3	66
22	60208	15	<0.2	1.80	30	80	10	3.47	<1	13	21	40	3.98	<10	1.39	721	2	0.04	2	1610	14	5	<20	55	0.04	<10	61	<10	2	45
23	60207	5	<0.2	2.00	20	55	10	4.88	1	14	20	37	4.19	<10	1.56	878	2	0.03	2	1590	14	10	<20	84	0.04	<10	60	30	3	58
24	60208	20	<0.2	1.81	20	50	<5	3.55	<1	16	19	94	4.31	<10	1.20	690	3	0.03	3	1880	14	<5	<20	55	0.02	<10	68	<10	1	81
25	60209	15	0.2	1.27	45	60	<5	4.18	<1	13	21	69	3.34	<10	1.00	658	6	0.04	2	1610	14	<5	<20	60	0.02	<10	70	<10	3	49

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AS- 97-1025

ECO-TECH LABORATORIES LTD.

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
26	60210	5	0.2	1.90	25	60	<5	3.38	<1	11	17	36	3.54	<10	1.50	760	1	0.02	2	1700	16	10	<20	55	0.02	<10	49	<10	3	59
27	60211	15	0.4	1.48	35	55	<5	4.88	<1	17	17	78	3.95	<10	1.12	817	3	0.03	3	1530	14	10	<20	74	0.02	<10	54	<10	1	52
28	60212	5	0.2	1.48	20	35	<5	3.79	<1	10	17	42	3.43	<10	1.14	821	2	0.03	2	1520	18	5	<20	58	0.02	<10	86	<10	2	62
29	60227	25	0.8	2.56	50	50	<5	8.89	<1	27	24	151	5.74	<10	2.29	1599	9	0.02	11	1500	16	15	<20	173	0.01	<10	156	<10	3	87
30	60228	30	0.6	2.04	80	55	<5	7.80	<1	27	24	102	6.51	<10	1.82	1394	7	0.01	9	1150	22	<5	<20	157	<0.01	<10	74	10	<1	70
31	60229	20	0.4	1.96	80	70	<5	7.40	<1	26	29	148	6.76	<10	1.38	1334	8	0.01	8	1190	14	5	<20	130	<0.01	<10	78	<10	<1	34
32	60230	35	0.6	1.58	110	70	<5	6.45	<1	38	27	152	6.44	<10	1.07	998	6	0.01	10	1300	18	<5	<20	113	<0.01	<10	73	20	<1	31
33	60231	40	0.8	1.54	105	65	<5	6.58	1	32	34	154	6.28	<10	1.05	1031	12	0.01	9	1220	22	<5	<20	124	<0.01	<10	57	<10	<1	108
34	60232	35	0.4	2.19	75	55	<5	4.93	<1	29	22	88	4.95	<10	1.79	991	5	0.01	5	1250	16	5	<20	114	<0.01	<10	73	<10	<1	54
35	60233	10	0.4	1.68	80	55	<5	8.95	3	19	23	82	4.75	<10	1.24	1187	5	0.02	6	940	10	10	<20	183	<0.01	<10	53	<10	<1	59

QC/DATA:

Repeat:																															
1	60054	55	<0.2	1.05	10	65	5	2.58	10	30	31	16	2.90	<10	0.93	584	<1	0.03	4	1650	24	10	<20	53	0.07	<10	53	<10	2	68	

Repeat:																															
1	60054	65	<0.2	1.18	5	80	5	2.77	<1	31	36	23	3.17	<10	1.01	604	<1	0.04	2	1750	12	5	<20	60	0.06	<10	60	<10	3	68	

10	60070	15	<0.2	1.82	10	165	5	1.29	<1	8	12	19	3.58	<10	1.58	679	<1	0.03	9	1780	14	10	<20	34	0.06	<10	38	<10	2	145	
18	60142	10	<0.2	1.18	10	75	5	2.53	<1	12	28	46	3.44	<10	0.82	810	<1	0.04	<1	1690	18	<5	<20	50	0.07	<10	62	<10	2	85	
Standard:																															
GEO97		130	1.4	1.73	60	160	<5	1.84	<1	20	81	80	4.22	<10	0.94	700	<1	0.03	24	730	22	<5	<20	62	0.11	<10	78	<10	5	77	

df/1009
XLS/97Tauton
Fax to Dino Vancouver 604-682-3982

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

22-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK- 97-1026

TEUTON RESOURCES CORPORATION
508-675 W. HASTINGS STREET
VANCOUVER, B.C.
V8C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 41
Sample Type: ROCK
PROJECT #: CLONE
SHIPMENT #: NONE GIVEN
Samples submitted by: NOT INDICATED

Values in ppm unless otherwise reported

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	C14+50E 23+75N	455	1.6	1.06	15	45	<5	0.90	<1	17	48	289	3.13	<10	0.70	251	<1	0.04	13	1600	10	<5	<20	31	0.13	<10	112	<10	3	24
2	C14+50E 24+00N	45	<0.2	1.84	<5	120	<5	0.85	<1	28	86	538	4.71	<10	1.83	283	<1	0.06	25	1210	10	<5	<20	48	0.34	<10	215	<10	8	20
3	C14+50E 24+25N	110	<0.2	2.80	15	35	<5	>10	<1	39	56	86	8.45	<10	2.80	2769	4	0.01	8	880	6	<5	<20	181	0.05	<10	118	<10	5	24
4	C14+50E 24+50N	805	5.2	1.67	<5	50	<5	0.89	<1	19	64	8239	5.24	<10	1.45	332	4	0.04	14	1360	14	<5	<20	38	0.16	<10	164	20	2	40
5	C14+50E 25+00N	70	<0.2	1.74	5	80	<5	1.49	<1	17	69	473	3.72	<10	1.54	574	<1	0.08	16	1580	12	<5	<20	38	0.15	<10	181	20	4	35
6	C14+50E 25+25N	>1000	4.6	2.05	75	75	<5	0.38	<1	87	89	734	>10	<10	1.78	562	4	0.03	27	1890	12	<5	<20	14	0.19	<10	374	<10	<1	38
7	C14+50E 25+50N	110	<0.2	3.80	5	60	<5	1.52	<1	29	186	274	7.70	<10	4.28	1570	<1	0.03	30	1350	18	<5	<20	25	0.16	<10	264	30	3	67
8	C14+50E 25+75N	65	<0.2	2.04	10	55	<5	1.03	<1	27	114	358	5.41	<10	2.07	484	<1	0.07	33	1880	12	<5	<20	32	0.22	<10	198	<10	5	34
9	C14+50E 26+00N	665	4.4	0.89	10	120	<5	0.17	2	44	88	1118	>10	<10	0.38	178	17	0.01	6	930	8	<5	<20	23	0.19	50	136	20	<1	24
10	C14+50E 26+25N	215	<0.2	2.83	10	90	<5	0.52	<1	41	68	138	8.81	<10	1.12	1547	12	0.01	20	2100	14	<5	<20	8	0.01	<10	123	<10	<1	32
11	C14+50E 26+50N	225	1.0	1.81	<5	80	<5	0.77	<1	22	135	525	7.87	<10	1.87	877	3	0.06	20	1850	10	<5	<20	26	0.20	<10	218	<10	<1	52
12	C14+50E 26+75N	195	0.8	1.64	<5	65	<5	1.40	<1	25	41	422	8.14	<10	1.17	858	7	0.05	13	5020	10	<5	<20	45	0.09	<10	203	<10	12	39
13	C14+50E 27+00N	>1000	7.2	1.43	110	170	<5	0.19	<1	18	15	950	>10	<10	0.48	334	20	0.02	1	1480	20	<5	<20	5	0.03	30	153	<10	<1	15
14	C14+50E 27+50N	5	<0.2	1.28	<5	70	<5	1.02	<1	17	43	84	3.70	<10	1.02	558	<1	0.07	8	1730	10	5	<20	48	0.16	<10	141	<10	5	35
15	C14+50E 27+75N	30	<0.2	1.16	<5	130	5	1.13	<1	15	58	31	3.05	<10	1.01	439	<1	0.07	9	1730	10	<5	<20	58	0.12	<10	117	10	4	21
16	C14+50E 28+00N	5	<0.2	1.64	20	85	<5	0.88	<1	14	57	116	4.23	<10	0.88	644	3	0.04	8	1800	12	<5	<20	14	0.03	<10	125	<10	6	30
17	C15+00E 23+00N	45	<0.2	0.64	5	50	<5	0.72	<1	9	50	148	1.50	<10	0.39	211	<1	0.06	7	1520	10	<5	<20	28	0.08	<10	53	10	4	17
18	C15+00E 23+75N	70	<0.2	1.62	<5	50	<5	1.07	<1	23	86	283	3.80	<10	1.47	311	<1	0.06	20	1480	10	<5	<20	37	0.21	<10	209	<10	5	31
19	C15+00E 24+00N	85	<0.2	1.87	<5	35	<5	1.24	<1	28	105	781	5.00	<10	2.17	484	<1	0.05	31	1850	12	<5	<20	44	0.17	<10	182	<10	3	32
20	C15+00E 24+25N	135	2.0	1.80	10	35	<5	3.01	<1	32	86	1288	3.92	<10	1.84	685	1	0.11	24	1770	10	10	<20	89	0.12	<10	105	30	3	30
21	C15+00E 24+75N	275	<0.2	1.82	<5	35	<5	1.25	<1	24	101	708	4.34	<10	1.78	413	<1	0.07	27	1710	12	<5	<20	41	0.21	<10	171	30	4	34
22	C15+00E 25+00N	25	<0.2	0.65	5	45	<5	0.88	<1	4	37	124	0.93	<10	0.31	143	<1	0.06	3	1300	10	5	<20	32	0.08	<10	38	<10	3	12
23	C15+00E 25+50N	10	<0.2	3.85	40	135	<5	0.83	<1	23	11	22	9.00	<10	1.98	1362	6	0.01	2	1390	20	<5	<20	9	0.01	<10	70	<10	7	44
24	C15+00E 26+00N	105	<0.2	1.77	10	60	<5	1.15	<1	26	117	372	4.91	<10	1.83	434	<1	0.07	38	1920	12	<5	<20	28	0.20	<10	191	<10	4	35
25	C15+00E 26+25N	180	<0.2	2.01	<5	50	<5	1.05	<1	37	141	844	5.80	<10	2.39	593	<1	0.04	41	1820	14	<5	<20	16	0.21	<10	184	20	4	41

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK- 97-1026

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	C15+00E 26+50N	80	<0.2	4.47	10	65	<5	2.12	<1	28	175	336	>10	<10	3.82	1409	5	0.02	50	2700	22	<5	<20	24	0.12	<10	254	<10	<1	84
27	C15+00E 26+75N	5	<0.2	2.36	<5	85	10	1.05	<1	28	138	74	8.09	<10	2.41	788	<1	0.04	38	1820	18	<5	<20	48	0.19	<10	184	30	4	33
28	C15+00E 27+00N	670	1.2	2.26	35	85	<5	0.81	<1	29	66	1445	9.26	<10	1.16	1320	9	0.04	11	1580	14	<5	<20	27	0.10	<10	153	10	<1	32
29	C15+00E 27+25N	255	7.0	1.20	20	85	<5	0.99	2	40	114	2218	7.95	<10	0.82	896	27	0.01	7	180	1092	<5	<20	8	0.03	<10	45	<10	<1	150
30	C15+00E 27+50N	30	<0.2	2.48	<5	55	<5	1.84	<1	28	111	413	5.72	<10	2.00	514	<1	0.05	30	2060	24	<5	<20	83	0.18	<10	207	20	3	34
31	C15+00E 27+75N	420	1.8	2.28	15	60	<5	1.84	<1	20	55	683	9.80	<10	0.96	581	13	0.03	6	1740	30	<5	<20	258	0.15	<10	120	<10	<1	32
32	C15+00E 28+00N	35	<0.2	2.26	<5	40	<5	1.67	<1	18	45	597	5.15	<10	2.02	825	1	0.07	9	1930	18	<5	<20	47	0.13	<10	207	<10	4	56
33	C15+50E 23+00N	135	<0.2	2.08	<5	35	<5	1.02	<1	38	89	890	5.59	<10	2.09	325	<1	0.05	34	1470	16	<5	<20	48	0.29	<10	220	<10	5	39
34	C15+50E 23+25N	75	<0.2	0.97	<5	40	<5	1.06	<1	14	58	312	2.48	<10	0.72	181	<1	0.05	13	1710	10	<5	<20	93	0.13	<10	118	10	4	15
35	C15+50E 23+50N	5	<0.2	1.73	<5	150	<5	2.04	<1	18	64	84	3.58	<10	1.51	786	<1	0.04	10	1640	12	<5	<20	59	0.08	<10	119	<10	4	31
36	C15+50E 24+25N	130	1.2	1.54	<5	55	<5	1.77	<1	14	82	813	3.88	<10	1.33	618	1	0.05	16	1800	10	5	<20	36	0.09	<10	136	<10	3	38
37	C15+50E 25+25N	155	1.0	3.57	5	95	<5	0.85	<1	31	173	1428	7.90	<10	4.22	1077	<1	0.04	40	2060	18	<5	<20	21	0.19	<10	260	20	2	99
38	C15+50E 25+75N	65	<0.2	1.89	5	65	<5	1.48	<1	21	98	492	3.94	<10	1.74	399	<1	0.07	30	1860	12	10	<20	33	0.18	<10	128	10	3	29
39	C15+50E 27+25N	80	1.2	2.60	20	70	<5	2.32	<1	57	129	1840	7.15	<10	2.80	1058	2	0.03	43	2390	22	<5	<20	35	0.13	<10	220	20	1	84
40	C15+50E 27+50N	40	0.4	3.05	10	95	<5	2.13	<1	47	115	1768	7.48	<10	3.00	1003	<1	0.04	45	2340	22	<5	<20	78	0.18	<10	221	<10	2	54
41	C15+50E 28+00N	5	0.2	1.99	75	95	<5	6.29	<1	25	48	71	5.12	<10	1.28	1095	4	0.02	28	2110	14	10	<20	108	<0.01	<10	88	<10	1	27

QC/DATA:

Repeat:																														
1	C14+50E 23+75N	505	1.8	1.08	15	40	<5	0.82	<1	19	48	289	3.29	<10	0.72	258	<1	0.04	14	1730	12	<5	<20	30	0.14	<10	118	<10	3	25
38	C15+50E 24+25N	195	1.4	1.49	5	55	<5	1.74	<1	14	84	834	3.83	<10	1.29	585	1	0.05	15	1600	12	<5	<20	33	0.09	<10	134	<10	3	40
Repeat:																														
1	C14+50E 23+75N	455	1.8	1.18	15	45	<5	0.88	<1	19	51	317	3.49	<10	0.74	262	<1	0.05	14	1740	12	<5	<20	32	0.14	<10	122	10	3	25
10	C14+50E 28+25N	260	<0.2	2.74	10	95	<5	0.53	<1	43	71	137	9.05	<10	1.15	1589	12	0.01	19	2200	18	<5	<20	7	0.01	<10	128	<10	<1	34
19	C15+00E 24+00N	80	<0.2	1.90	<5	35	<5	1.27	<1	26	108	771	5.07	<10	2.20	488	<1	0.05	31	1660	12	<5	<20	48	0.18	<10	185	20	3	32
36	C15+50E 24+25N	140	1.2	1.55	<5	55	<5	1.83	<1	15	84	822	3.75	<10	1.35	630	1	0.05	15	1680	12	5	<20	33	0.09	<10	139	30	4	41
Standard:																														
GEO'97		145	1.0	1.78	65	155	<5	1.73	<1	20	84	87	4.28	<10	0.93	685	<1	0.03	24	710	22	<5	<20	60	0.12	<10	81	<10	5	73
GEO'97		155	1.0	1.74	60	150	<5	1.75	<1	20	81	85	4.24	<10	0.94	688	<1	0.03	22	720	20	5	<20	58	0.11	<10	80	20	5	74

dt/1020
XLS/977euton
Fax to Dino Vancouver 604-682-3882

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

30-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK-97-1068

TEUTON RESOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 37
Sample Type: Core
PROJECT #: Clone
SHIPMENT #: None Given
Samples submitted by: Teuton

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	60061	10	<0.2	1.62	<5	75	<5	2.40	<1	8	17	11	4.01	<10	1.41	785	1	0.03	2	1530	4	<5	<20	51	0.07	<10	45	<10	1	58
2	60062	10	<0.2	1.60	10	60	<5	2.49	<1	10	10	15	3.55	<10	1.17	729	<1	0.02	<1	1590	8	<5	<20	39	0.07	<10	41	10	3	105
3	60063	25	<0.2	1.43	15	90	<5	1.97	<1	10	18	14	3.33	<10	0.98	608	<1	0.03	<1	1660	8	5	<20	46	0.06	<10	41	<10	4	92
4	60064	5	<0.2	1.58	10	65	<5	1.81	<1	13	14	25	3.15	<10	1.19	708	1	0.03	<1	1820	8	5	<20	41	0.08	<10	48	<10	3	400
5	60065	5	<0.2	1.88	<5	95	<5	3.05	2	17	16	47	3.47	<10	1.54	997	<1	0.02	<1	1560	6	<5	<20	54	0.07	<10	49	<10	2	544
6	60066	5	<0.2	2.05	15	380	<5	1.89	<1	12	15	66	3.92	<10	1.47	887	<1	0.02	<1	1650	12	<5	<20	38	0.07	<10	47	<10	2	606
7	60067	10	<0.2	1.99	20	425	<5	3.13	2	36	18	24	4.20	<10	1.50	1124	<1	0.02	<1	1570	12	<5	<20	49	0.07	<10	52	<10	2	716
8	60068	5	<0.2	0.97	10	100	<5	2.02	6	8	15	61	2.53	<10	0.42	460	2	0.02	2	1870	12	<5	<20	46	0.02	<10	31	<10	3	536
9	60090	10	0.8	1.05	20	80	<5	0.73	1	10	17	82	2.73	<10	0.51	204	3	0.02	2	1770	10	<5	<20	19	<0.01	<10	28	10	2	107
10	60091	40	1.2	1.27	25	100	<5	1.45	<1	10	17	124	2.95	<10	0.76	496	3	0.02	<1	1480	24	5	<20	32	<0.01	<10	25	<10	2	80
11	60092	60	<0.2	1.83	20	315	<5	3.05	2	10	14	190	3.88	<10	1.11	737	4	0.02	<1	1640	40	5	<20	85	0.03	<10	50	<10	1	93
12	60093	145	0.4	1.54	20	95	<5	3.01	2	16	19	193	3.39	<10	1.00	850	3	0.03	<1	1570	24	5	<20	62	0.02	<10	39	10	2	96
13	60094	30	<0.2	1.39	20	230	<5	2.87	<1	24	18	69	3.11	<10	0.93	563	3	0.03	<1	1630	14	<5	<20	89	0.01	<10	43	<10	1	59
14	60095	>1000	0.4	1.50	115	100	<5	2.95	<1	97	15	241	3.39	<10	0.92	658	3	0.02	<1	1580	10	5	<20	85	0.02	<10	33	<10	2	90
15	60096	315	<0.2	1.83	55	285	<5	3.07	<1	41	22	103	3.38	<10	1.19	603	3	0.02	2	1540	10	<5	<20	89	<0.01	<10	28	<10	1	68
16	60097	75	<0.2	1.84	30	315	<5	4.34	<1	19	17	141	3.45	<10	1.28	706	3	0.02	<1	1550	6	5	<20	105	0.01	<10	37	<10	2	74
17	60098	30	<0.2	1.62	55	230	<5	4.36	<1	28	23	143	3.88	<10	1.13	732	4	0.02	1	1500	10	<5	<20	152	0.01	<10	40	<10	2	61
18	60099	155	<0.2	1.98	80	80	<5	4.12	<1	48	18	130	4.20	<10	1.38	774	3	0.02	<1	1520	4	<5	<20	109	0.01	<10	50	<10	<1	75
19	60131	5	<0.2	1.49	15	75	<5	1.10	<1	12	22	37	5.26	<10	1.03	1012	1	0.04	2	1820	14	<5	<20	33	0.08	<10	73	<10	<1	102
20	60132	10	<0.2	1.11	15	80	<5	1.70	<1	10	25	14	4.60	<10	0.66	758	2	0.04	1	1640	12	<5	<20	49	0.07	<10	75	<10	2	70
21	60133	10	0.4	1.42	10	100	<5	1.42	<1	20	40	116	4.10	<10	0.98	788	1	0.04	<1	1480	10	<5	<20	87	0.07	<10	61	<10	<1	101
22	60134	35	<0.2	1.58	15	80	5	1.47	<1	20	24	30	5.23	<10	1.22	824	2	0.03	<1	1540	14	<5	<20	40	0.08	<10	86	<10	<1	107
23	60135	65	<0.2	1.67	15	85	<5	2.67	1	23	28	34	5.01	<10	1.27	1104	2	0.02	1	1510	14	<5	<20	46	0.07	<10	82	<10	<1	248
24	60136	5	<0.2	1.38	15	95	10	1.11	<1	27	17	31	4.88	<10	0.94	827	2	0.03	3	1590	12	<5	<20	30	0.08	<10	69	<10	2	197
25	60137	5	<0.2	1.44	15	85	<5	2.22	2	17	24	6	5.08	<10	1.01	890	2	0.03	2	1580	8	<5	<20	44	0.06	<10	71	<10	2	115

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1068

ECO-TECH LABORATORIES LTD.

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	60145	15	<0.2	1.27	15	470	<5	2.48	<1	8	18	88	4.29	<10	1.04	758	1	0.03	<1	1590	8	5	<20	75	0.08	<10	75	<10	2	43
27	60146	105	<0.2	1.57	15	150	<5	3.07	<1	71	17	18	4.14	<10	1.43	828	<1	0.03	<1	1810	8	<5	<20	59	0.07	<10	67	<10	2	42
28	60147	5	<0.2	1.91	15	60	10	1.88	<1	13	13	4	4.70	<10	1.68	826	<1	0.03	2	1620	6	<5	<20	39	0.08	<10	83	<10	<1	46
29	60148	5	<0.2	1.78	10	55	5	2.17	<1	12	17	7	4.46	<10	1.53	747	<1	0.03	2	1820	10	<5	<20	48	0.08	<10	66	<10	1	62
30	60149	385	<0.2	1.31	25	55	<5	3.03	<1	63	14	41	3.57	<10	0.89	590	<1	0.03	<1	1640	14	5	<20	77	0.07	<10	59	20	2	76
31	60150	5	<0.2	1.02	10	55	<5	3.57	<1	20	24	12	2.91	<10	0.83	548	<1	0.04	1	1690	8	<5	<20	83	0.07	<10	71	<10	3	46
32	60151	30	<0.2	1.28	15	55	5	2.70	<1	22	16	5	2.93	<10	1.15	576	<1	0.04	<1	1700	8	5	<20	73	0.08	<10	87	<10	3	52
33	60152	10	<0.2	1.38	15	40	<5	3.08	<1	25	23	15	3.20	<10	1.29	692	<1	0.05	2	1810	10	10	<20	82	0.08	<10	73	<10	2	81
34	60153	30	<0.2	1.28	15	55	<5	3.08	<1	36	17	43	2.99	<10	1.03	654	<1	0.05	1	1880	12	5	<20	76	0.08	<10	83	20	3	70
35	60154	140	<0.2	1.42	15	85	<5	2.86	<1	28	19	20	3.15	<10	1.12	704	<1	0.04	<1	1670	6	<5	<20	60	0.08	<10	54	<10	2	108
36	60155	180	<0.2	1.14	10	115	<5	2.49	1	27	14	96	3.15	<10	0.76	630	<1	0.03	1	1870	8	10	<20	49	0.07	<10	55	<10	3	184
37	60156	>1000	1.4	1.13	25	110	<5	2.12	<1	62	11	38	4.11	<10	0.74	659	2	0.03	<1	1650	14	<5	<20	46	0.08	<10	56	<10	2	185

QC/DATA:
Resplit:

1	60061	10	<0.2	1.89	10	75	<5	2.51	<1	10	24	10	4.14	<10	1.44	806	<1	0.03	2	1860	8	5	<20	49	0.08	<10	47	<10	2	61
---	-------	----	------	------	----	----	----	------	----	----	----	----	------	-----	------	-----	----	------	---	------	---	---	-----	----	------	-----	----	-----	---	----

36	80155	240	<0.2	1.14	10	115	<5	2.55	1	27	19	100	3.13	<10	0.76	636	<1	0.03	<1	1670	8	<5	<20	54	0.07	<10	56	<10	2	166	
Repeat:																															
1	60081	5	<0.2	1.77	<5	70	<5	2.35	<1	8	15	11	3.92	<10	1.37	788	<1	0.03	<1	1500	6	10	<20	48	0.07	<10	44	<10	<1	59	
10	60091	50	1.2	1.28	20	95	<5	1.48	<1	11	18	125	2.96	<10	0.77	499	3	0.02	2	1480	28	5	<20	33	<0.01	<10	25	10	2	79	
19	80131	5	<0.2	1.48	15	75	5	1.10	<1	12	22	36	5.27	<10	1.03	1018	2	0.04	1	1810	14	<5	<20	33	0.07	<10	73	<10	<1	102	
36	60155	190	<0.2	1.16	10	115	<5	2.53	1	28	15	99	3.21	<10	0.77	639	<1	0.03	2	1680	8	10	<20	51	0.07	<10	57	<10	3	186	
Standard:																															
GEO'97		120	1.2	1.90	50	165	<5	1.79	<1	20	59	80	4.46	<10	0.97	692	<1	0.03	25	660	20	<5	<20	86	0.13	<10	80	<10	4	71	
GEO'97		136	1.2	1.88	60	155	<5	1.79	<1	20	59	81	4.44	<10	0.96	688	<1	0.03	25	710	24	<5	<20	81	0.12	<10	78	<10	5	77	

df/1068
XLS/97Teuton
Fax to Dino Vancouver 604-682-3982

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AK 97-1034

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

3-Oct-97

ATTENTION: DINO CREMONESE

No. of samples received: 33

Sample Type: Core

PROJECT #: Clone

SHIPMENT #: CL-13

P.O.#: None Given

Samples submitted by: Dale Roberts

ET #.	Tag #	Au (g/t)	Au (oz/t)	Co (%)
1	60531	2.84	0.083	-
7	60537	3.03	0.088	-
26	60556	2.39	0.070	0.062

QC/DATA:

Standard:

STD-M	1.45	0.042	-
SU-1a	-	-	0.041

XLS/97Teuton
Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

24-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK-97-1034

TEUTON RESOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 33
Sample Type: Core
PROJECT #: Clone
SHIPMENT #: CL-13
P.O.#: None Given
Samples submitted by: Dale Roberts

Values in ppm unless otherwise reported

El #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	60531	>1000	2.4	2.24	905	85	<5	1.87	<1	192	28	385	5.13	<10	1.50	919	5	0.03	3	1470	12	<5	<20	38	<0.01	<10	84	<10	<1	80
2	60532	50	0.4	1.75	190	80	<5	2.83	<1	30	21	97	3.88	<10	1.32	753	4	0.05	2	1390	8	10	<20	51	<0.01	<10	88	<10	1	48
3	60533	45	0.4	1.71	85	85	<5	3.04	<1	23	23	98	3.85	<10	1.24	758	4	0.07	2	1480	10	<5	<20	62	<0.01	<10	108	<10	2	43
4	60534	135	0.8	1.60	130	50	<5	3.52	<1	38	30	117	4.19	<10	1.12	723	8	0.05	4	1060	10	5	<20	84	0.01	<10	98	<10	2	49
5	60535	50	0.8	2.01	85	80	<5	1.74	<1	38	53	213	5.42	<10	1.42	838	6	0.04	3	1060	12	<5	<20	32	0.02	<10	109	<10	2	85
6	60536	560	1.0	1.73	860	80	<5	3.83	<1	89	28	230	4.77	<10	1.22	841	6	0.05	3	1200	10	<5	<20	55	0.02	<10	120	<10	2	55
7	60537	>1000	0.4	4.28	2840	80	<5	5.28	<1	194	44	211	>10	<10	3.80	1631	8	0.03	24	1490	8	<5	<20	81	0.04	<10	337	<10	<1	95
8	60538	55	<0.2	4.13	205	90	<5	6.89	<1	56	41	193	8.85	<10	4.34	1901	3	0.04	28	1480	8	<5	<20	133	0.14	<10	274	<10	<1	88
9	60539	15	<0.2	3.71	75	55	5	8.44	<1	42	31	127	7.38	<10	3.88	1508	1	0.04	23	1610	4	<5	<20	128	0.17	<10	225	10	3	80
10	60540	25	<0.2	3.09	65	65	<5	3.57	<1	42	20	162	6.96	<10	3.16	1080	<1	0.05	14	2050	10	<5	<20	101	0.18	<10	204	<10	5	56
11	60541	40	<0.2	3.89	80	55	<5	5.10	<1	44	41	189	7.97	<10	3.87	1445	3	0.05	27	1550	8	<5	<20	108	0.20	<10	244	<10	2	65
12	60542	25	<0.2	3.96	50	55	5	7.10	<1	43	29	185	8.01	<10	4.07	1868	8	0.04	24	1650	4	<5	<20	171	0.18	<10	285	<10	3	71
13	60543	20	<0.2	4.95	50	55	10	8.14	<1	47	28	185	9.72	<10	4.80	2233	3	0.03	27	1610	4	<5	<20	226	0.18	<10	378	<10	2	94
14	60544	25	<0.2	4.13	50	90	5	6.50	<1	41	24	177	8.77	<10	4.03	1848	8	0.03	19	1800	8	<5	<20	151	0.16	<10	328	10	<1	70
15	60545	15	<0.2	3.73	45	75	5	4.70	<1	38	13	146	7.64	<10	3.56	1458	4	0.03	7	2140	4	<5	<20	114	0.16	<10	291	<10	3	83
16	60546	35	<0.2	3.73	30	80	5	6.69	<1	39	47	126	7.70	<10	3.54	1665	2	0.02	13	2030	8	<5	<20	156	0.13	<10	280	<10	3	81
17	60547	55	<0.2	3.71	35	55	<5	4.19	<1	36	18	116	7.18	<10	3.82	1482	<1	0.03	8	2140	8	<5	<20	132	0.15	<10	234	<10	4	86
18	60548	15	<0.2	3.84	45	55	<5	5.10	<1	40	12	161	7.88	<10	4.04	1621	2	0.04	9	1980	10	<5	<20	122	0.15	<10	253	<10	3	64
19	60549	10	<0.2	4.36	35	50	10	4.95	<1	38	16	108	8.48	<10	4.48	1690	<1	0.05	12	2000	10	<5	<20	108	0.20	<10	255	<10	2	88
20	60550	95	<0.2	4.17	45	55	<5	5.12	<1	36	14	181	7.97	<10	4.19	1591	2	0.04	11	2080	10	<5	<20	134	0.15	<10	256	<10	4	88
21	60551	40	<0.2	4.63	35	45	15	5.84	<1	45	16	88	8.89	<10	4.85	1901	2	0.03	14	1900	10	<5	<20	135	0.14	<10	301	10	4	90
22	60552	45	<0.2	3.75	45	65	5	3.74	<1	40	9	127	7.74	<10	3.78	1375	20	0.03	5	2600	12	<5	<20	105	0.17	<10	257	10	5	58
23	60553	450	<0.2	4.29	1540	55	<5	4.53	<1	152	21	157	8.75	<10	4.38	1435	7	0.03	12	2140	14	<5	<20	118	0.13	<10	287	<10	1	64
24	60554	275	<0.2	4.35	1330	55	<5	4.75	<1	141	27	188	8.81	<10	4.41	1421	9	0.03	13	2180	18	<5	<20	125	0.13	<10	295	10	2	63
25	60555	30	<0.2	4.82	85	45	5	6.87	<1	43	88	96	8.67	<10	5.13	1825	8	0.03	22	1820	12	<5	<20	200	0.09	<10	325	<10	2	89

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1034

ECO-TECH LABORATORIES LTD.

El #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
26	60556	>1000	1.0	4.70	9675	58	<5	5.29	<1	589	17	285	>10	<10	4.41	1742	9	0.03	10	2210	18	<5	<20	145	0.05	<10	325	10	<1	88
27	60557	20	<0.2	4.45	60	50	<5	6.96	<1	40	89	100	8.16	<10	4.56	2174	3	0.03	27	1600	10	<5	<20	188	0.14	<10	298	<10	<1	91
28	60558	45	<0.2	4.43	50	50	<5	5.39	1	37	44	149	9.07	<10	4.18	1958	8	0.03	18	1810	18	<5	<20	157	0.10	<10	318	10	<1	158
29	60559	615	1.4	2.88	1805	80	<5	4.31	<1	79	26	194	7.22	<10	2.12	1628	12	0.03	7	1530	368	<5	<20	80	0.05	<10	162	<10	<1	908
30	60580	120	0.6	2.08	265	50	<5	2.53	<1	23	27	102	4.86	<10	1.48	1078	28	0.04	2	1580	44	<5	<20	58	0.02	<10	102	<10	<1	142
31	60581	85	0.4	3.18	80	55	<5	4.40	<1	26	17	174	7.58	<10	2.86	1482	18	0.03	4	1840	40	<5	<20	155	0.07	<10	199	10	<1	90
32	60582	85	0.2	5.46	1850	80	10	5.39	<1	110	35	163	>10	<10	5.02	1957	6	0.02	11	1880	218	<5	<20	161	0.10	<10	290	<10	<1	588
33	60583	40	<0.2	5.32	45	65	10	3.72	<1	38	37	174	>10	<10	4.95	1822	5	0.03	11	2120	20	<5	<20	153	0.10	<10	321	<10	<1	95

QC/DATA:

Repeat:	El #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	60531	>1000	2.6	2.38	1005	85	<5	1.76	<1	206	26	385	5.83	<10	1.58	1013	5	0.03	3	1510	14	<5	<20	38	0.01	<10	88	<10	<1	84	

Repeat:	El #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	60531	>1000	2.2	2.31	820	85	<5	1.72	<1	197	29	383	5.28	<10	1.53	942	6	0.04	4	1530	14	<5	<20	33	0.01	<10	86	20	<1	83	
10	60540	30	<0.2	3.08	70	65	<5	3.54	<1	42	20	158	6.95	<10	3.15	1058	<1	0.05	14	2070	8	5	<20	101	0.17	<10	200	<10	4	58	

19	60549	15	<0.2	4.27	40	45	15	4.87	<1	38	18	104	8.41	<10	4.38	1871	<1	0.04	12	2010	12	<5	<20	105	0.18	<10	249	<10	2	68
28	60558	40	<0.2	4.68	55	50	5	5.64	<1	41	46	158	9.58	<10	4.38	2058	10	0.03	19	1900	20	<5	<20	164	0.09	<10	333	30	<1	173
Standard:																														
GEO97		140	1.4	1.78	70	185	<5	1.74	<1	20	80	83	4.14	<10	0.85	702	<1	0.03	22	880	28	<5	<20	80	0.11	<10	79	<10	5	71

df/1034
XLS/97Teuton
Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

23-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AK-97-1035

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 42
Sample Type: Core
PROJECT #: Clone
SHIPMENT #: CL-6
P.O.#: None Given
Samples submitted by: Dale Roberts

Values in ppm unless otherwise reported

El#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	80157	150	<0.2	1.25	20	85	<5	2.76	<1	17	28	15	2.96	<10	0.78	682	1	0.03	3	1800	8	5	<20	58	0.08	<10	40	<10	2	111
2	80158	30	<0.2	1.65	20	110	5	1.27	<1	9	21	16	3.48	<10	1.24	614	<1	0.03	3	1620	12	5	<20	32	0.07	<10	44	<10	1	133
3	80159	10	<0.2	1.81	10	75	<5	1.51	<1	8	24	93	3.45	<10	1.48	681	<1	0.04	2	1840	12	10	<20	37	0.06	<10	48	<10	1	78
4	80160	5	<0.2	1.83	10	75	<5	1.83	<1	8	21	98	3.15	<10	1.54	684	<1	0.04	4	1800	12	15	<20	55	0.07	<10	50	10	1	73
5	80161	10	<0.2	1.57	5	55	<5	2.08	1	6	23	75	2.87	<10	1.48	585	<1	0.04	2	1480	10	10	<20	43	0.06	<10	44	10	<1	28
6	80162	5	<0.2	1.99	10	75	<5	2.86	<1	7	18	28	3.23	<10	1.71	630	<1	0.05	2	1590	14	15	<20	59	0.08	<10	49	10	1	34
7	80183	15	0.2	1.49	5	90	<5	2.98	<1	7	16	178	2.81	<10	1.31	597	<1	0.03	1	1470	12	5	<20	50	0.06	<10	34	<10	2	74
8	80184	5	<0.2	1.71	10	75	<5	1.84	<1	8	18	127	3.04	<10	1.41	540	<1	0.03	2	1690	12	15	<20	44	0.06	<10	43	10	2	39
9	80185	10	<0.2	1.81	10	105	<5	2.15	<1	8	16	45	2.85	<10	1.36	524	<1	0.04	2	1600	10	5	<20	58	0.06	<10	40	<10	2	28
10	80186	5	<0.2	1.43	<5	120	<5	2.96	<1	8	20	37	3.11	<10	1.12	533	<1	0.04	2	1800	12	10	<20	68	0.07	<10	53	10	4	24
11	80187	5	<0.2	1.82	5	80	<5	2.77	<1	8	18	50	2.88	<10	1.31	534	<1	0.03	2	1540	10	5	<20	84	0.04	<10	41	<10	3	25
12	80188	225	0.4	1.15	15	110	<5	2.36	<1	14	14	102	2.25	<10	0.75	597	1	0.02	2	1450	10	5	<20	53	0.02	<10	29	<10	2	166
13	80189	10	<0.2	1.10	<5	70	<5	2.59	3	5	45	22	2.27	<10	0.87	622	3	0.03	2	1310	8	<5	<20	48	0.02	<10	42	<10	2	47
14	80170	5	<0.2	1.50	15	80	<5	2.23	<1	7	24	28	2.87	<10	1.12	718	1	0.04	3	1610	8	10	<20	50	0.04	<10	51	<10	3	54
15	80171	10	<0.2	1.13	40	55	<5	1.79	<1	7	16	34	2.57	<10	0.84	618	2	0.03	2	1280	10	10	<20	34	0.02	<10	34	<10	<1	55
16	80172	10	<0.2	1.60	10	100	<5	2.07	<1	21	22	73	3.51	<10	1.17	745	1	0.04	3	1620	10	<5	<20	49	0.05	<10	55	<10	3	72
17	80173	5	<0.2	1.29	10	70	<5	2.00	<1	12	28	57	2.96	<10	0.93	651	<1	0.03	3	1690	8	<5	<20	52	0.05	<10	62	<10	3	71
18	80174	5	<0.2	1.43	20	70	<5	2.16	3	10	21	143	3.01	<10	1.13	726	2	0.04	3	1620	18	<5	<20	54	0.04	<10	59	10	2	93
19	80175	5	<0.2	1.50	15	75	<5	2.35	3	9	24	143	3.38	<10	1.12	768	2	0.05	3	1590	16	10	<20	56	0.03	<10	67	<10	2	111
20	80176	5	<0.2	1.86	5	135	<5	2.11	<1	9	17	18	3.58	<10	1.26	812	2	0.04	3	1640	28	<5	<20	57	0.05	<10	54	<10	2	159
21	80177	5	<0.2	1.88	10	70	5	2.23	<1	7	17	7	3.52	<10	1.28	814	2	0.04	2	1590	18	5	<20	58	0.04	<10	50	<10	1	100
22	80178	5	<0.2	1.64	5	90	5	1.86	<1	9	14	5	3.34	<10	1.21	720	1	0.04	3	1560	10	10	<20	47	0.03	<10	42	<10	1	91
23	80179	10	<0.2	1.48	30	95	<5	3.76	<1	45	18	60	3.07	<10	0.86	747	2	0.03	2	1600	14	<5	<20	85	0.03	<10	38	10	3	70
24	80180	980	0.4	1.15	10	85	<5	4.11	5	11	12	344	2.79	<10	0.76	735	2	0.02	3	1260	16	10	<20	72	0.02	<10	33	<10	2	151
25	80181	180	0.4	1.81	10	85	<5	4.15	5	11	17	248	3.17	<10	0.88	855	2	0.02	2	1560	22	<5	<20	97	0.02	<10	35	<10	2	238

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1035

ECO-TECH LABORATORIES LTD.

El#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
26	80182	15	<0.2	1.51	20	90	<5	3.18	2	21	15	47	2.98	<10	0.94	782	2	0.04	2	1640	22	<5	<20	84	0.02	<10	40	<10	2	159
27	80183	205	<0.2	1.14	65	190	<5	3.50	2	70	19	60	2.88	<10	0.89	844	<1	0.04	1	1700	14	<5	<20	83	0.04	<10	42	10	3	91
28	80184	35	<0.2	1.45	10	90	5	4.53	<1	14	13	28	2.85	<10	0.96	804	<1	0.03	2	1570	10	<5	<20	93	0.04	<10	33	<10	4	43
29	80185	55	<0.2	1.29	10	85	<5	6.21	<1	31	15	85	2.85	<10	0.87	883	1	0.03	2	1530	8	<5	<20	118	0.04	<10	38	10	4	45
30	80188	80	0.4	1.23	75	70	<5	4.52	<1	75	19	319	2.95	<10	0.85	735	1	0.03	3	1550	8	10	<20	80	0.04	<10	45	10	3	83
31	80187	140	<0.2	1.19	35	275	<5	4.73	<1	35	20	182	2.45	<10	0.78	695	2	0.03	2	1560	8	5	<20	130	0.02	<10	36	10	2	63
32	80188	125	<0.2	1.27	10	70	<5	3.61	<1	21	20	103	2.71	<10	0.89	801	2	0.02	2	1540	6	<5	<20	105	0.01	<10	35	<10	<1	52
33	80189	15	<0.2	1.39	10	170	<5	4.48	<1	15	25	41	2.99	<10	1.00	735	1	0.04	3	1610	8	<5	<20	131	0.02	<10	52	10	<1	49
34	80190	505	0.4	1.43	35	90	<5	4.73	<1	24	27	113	3.18	<10	0.88	701	3	0.03	3	1430	12	<5	<20	141	<0.01	<10	38	10	<1	75
35	80191	710	0.4	1.62	110	680	<5	3.84	<1	82	30	89	3.08	<10	1.07	816	3	0.02	2	1490	28	5	<20	185	0.02	<10	34	10	<1	83
36	80192	75	0.2	1.65	55	105	<5	3.53	<1	47	23	119	3.08	<10	1.04	587	3	0.02	3	1540	14	5	<20	93	0.02	<10	35	<10	<1	42
37	80193	100	0.2	1.84	15	110	<5	3.68	<1	11	20	53	3.14	<10	1.50	635	3	0.03	2	1610	12	10	<20	91	<0.01	<10	33	<10	1	46
38	80194	15	<0.2	1.55	30	80	<5	3.80	<1	12	22	35	2.94	<10	1.13	692	2	0.03	2	1800	10	<5	<20	118	0.01	<10	39	<10	1	47
39	80195	10	<0.2	1.55	25	65	<5	3.78	<1	10	20	48	3.14	<10	1.08	687	3	0.04	2	1610	14	<5	<20	108	<0.01	<10	55	<10	<1	63
40	80196	30	0.2	1.47	20	70	<5	2.86	<1	13	29	75	3.48	<10	0.97	644	3	0.04	2	1650	14	<5	<20	88	<0.01	<10	57	<10	<1	58
41	80197	10	<0.2	1.43	10	50	<5	3.70	<1	7	22	20	2.87	<10	0.86	697	2	0.05	3	1870	16	5	<20	91	<0.01	<10	65	<10	<1	88

42	60198	10	<0.2	1.39	20	45	<5	4.21	<1	8	24	28	2.98	<10	0.88	745	2	0.06	3	1800	18	<5	<20	98	<0.01	<10	64	<10	<1	83	
QC/DATA:																															
Resplit:																															
1	60157	140	<0.2	1.18	30	80	10	2.68	<1	18	24	15	2.92	<10	0.77	683	<1	0.02	3	1810	10	5	<20	53	0.05	<10	37	<10	2	111	
38	60192	100	0.2	1.83	55	105	<5	3.50	<1	47	22	117	3.04	<10	1.02	581	2	0.02	2	1570	18	5	<20	88	0.02	<10	35	<10	<1	42	
Repeat:																															
1	60157	145	<0.2	1.23	25	80	5	2.74	<1	17	28	15	2.91	<10	0.78	677	<1	0.03	3	1590	8	<5	<20	54	0.05	<10	38	<10	2	108	
10	60188	5	<0.2	1.42	<5	125	<5	2.90	<1	7	20	36	3.04	<10	1.10	521	1	0.05	3	1580	10	5	<20	68	0.08	<10	52	<10	4	23	
19	60175	10	<0.2	1.51	10	70	<5	2.40	4	10	24	148	3.48	<10	1.18	791	2	0.04	3	1640	16	5	<20	54	0.03	<10	67	<10	1	118	
38	60182	95	0.4	1.60	80	95	<5	3.39	<1	45	21	112	2.85	<10	0.94	557	2	0.02	2	1500	16	<5	<20	84	0.01	<10	31	<10	<1	40	
Standard:																															
GEO'97		130	1.4	1.71	70	180	<5	1.84	<1	19	58	79	3.08	<10	0.91	673	<1	0.03	24	670	24	<5	<20	59	0.11	<10	75	20	6	68	
GEO'97		145	1.4	1.73	85	180	<5	1.82	<1	19	58	80	3.99	<10	0.92	683	<1	0.03	22	680	24	<5	<20	60	0.11	<10	75	20	6	68	

df/1034
XLS/977auton
Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AK 97-1036

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

25-Sep-97

ATTENTION: DINO CREMONESE

No. of samples received: 56

Sample type: CORE

PROJECT: # CLONE

SHIPMENT: # CL-12

Samples submitted by: DALE ROBERTS

ET #.	Tag #	Au (g/t)	Au (oz/t)	As (%)	Co (%)
12	60486	12.20	0.356	-	0.119
17	60491	1.24	0.036	-	0.029
18	60492	1.45	0.042	-	-
49	60523	1.99	0.058	-	-
55	60529	10.48	0.306	4.76	0.210
56	60530	21.00	0.612	1.05	0.158

QC/DATA:

Standard:

STD-M	1.42	0.041	-	-
CD-1	-	-	0.66	-
MP-1a	-	-	-	0.041

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

XLS/97Teuton

Fax to Dino Vancouver 604-682-3992

24-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK- 97-1038

TEUTON RESOURCES CORPORATION
508-875 W. HASTINGS STREET
VANCOUVER, B.C.
V8C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 56
Sample Type: CORE
PROJECT #: CLONE
SHIPMENT #: CL-12
Samples submitted by: DALE ROBERTS

Values in ppm unless otherwise reported

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	60475	140	<0.2	2.36	35	90	<5	6.33	<1	40	50	229	8.12	<10	2.24	1406	3	0.08	15	1480	2	<5	<20	78	0.14	<10	207	20	<1	58
2	60476	25	<0.2	3.15	30	70	<5	1.91	2	48	44	258	9.84	<10	2.98	1309	5	0.06	18	1750	8	<5	<20	33	0.12	<10	258	40	<1	72
3	60477	20	<0.2	3.12	15	65	5	4.05	<1	38	48	97	8.52	<10	3.04	1429	<1	0.08	15	1740	<2	<5	<20	80	0.16	<10	241	<10	<1	55
4	60478	140	<0.2	3.07	25	55	10	4.15	<1	46	85	114	8.56	<10	3.18	1330	1	0.07	19	1700	<2	<5	<20	63	0.17	<10	215	<10	<1	50
5	60479	15	<0.2	3.42	20	45	10	3.85	<1	42	70	101	7.80	<10	3.78	1433	<1	0.07	20	1780	2	<5	<20	71	0.17	<10	204	<10	<1	50
6	60480	35	<0.2	2.70	30	45	<5	5.30	<1	40	53	143	6.68	<10	2.99	1314	<1	0.07	18	1670	<2	<5	<20	88	0.16	<10	198	<10	<1	40
7	60481	75	<0.2	2.93	40	65	<5	4.60	<1	38	56	128	7.69	<10	3.45	1287	<1	0.08	16	1700	2	<5	<20	86	0.20	<10	194	<10	<1	44
8	60482	25	<0.2	3.17	40	80	5	4.49	<1	37	58	81	7.83	<10	3.71	1328	<1	0.08	17	1740	4	<5	<20	86	0.19	<10	225	<10	1	47
9	60483	55	<0.2	3.17	35	45	15	5.13	<1	32	58	60	7.39	<10	3.76	1311	<1	0.05	16	1660	2	<5	<20	74	0.19	<10	204	30	<1	45
10	60484	20	<0.2	3.55	30	65	10	4.63	<1	27	58	121	8.57	<10	3.93	1209	<1	0.05	17	1840	<2	<5	<20	63	0.18	<10	238	<10	<1	44
11	60485	40	<0.2	2.70	65	100	<5	1.51	<1	58	43	338	8.87	<10	2.76	702	3	0.04	8	2010	4	<5	<20	31	0.11	<10	191	<10	<1	38
12	60486	>1000	0.4	3.17	990	85	<5	4.37	<1	983	39	968	9.38	<10	3.08	882	12	0.02	8	1550	4	<5	<20	56	0.11	<10	228	<10	<1	64
13	60487	35	<0.2	4.54	50	55	<5	3.58	<1	82	13	131	8.74	<10	4.63	1176	<1	0.05	14	1700	2	<5	<20	54	0.17	<10	237	<10	<1	51
14	60488	5	<0.2	4.15	35	135	10	4.38	<1	37	28	142	8.31	<10	4.17	1188	<1	0.05	15	1780	<2	5	<20	78	0.19	<10	234	<10	2	46
15	60489	15	<0.2	3.84	45	185	<5	8.95	<1	37	27	128	7.87	<10	3.49	1873	<1	0.05	20	1570	<2	<5	<20	114	0.17	<10	253	20	9	57
16	60490	130	<0.2	3.18	80	80	<5	7.73	<1	58	33	212	7.24	<10	2.82	1428	<1	0.05	17	1360	4	<5	<20	110	0.17	<10	212	30	4	53
17	60491	>1000	0.4	2.20	1370	85	<5	4.13	<1	285	25	645	5.07	<10	1.68	873	2	0.03	2	980	10	<5	<20	73	0.07	<10	112	20	2	53
18	60492	>1000	0.2	1.99	950	85	<5	3.29	<1	187	30	199	4.86	<10	1.38	743	2	0.06	3	1070	10	<5	<20	69	0.08	<10	95	<10	2	43
19	60493	355	<0.2	2.07	70	90	<5	4.02	<1	44	30	129	4.35	<10	1.43	852	<1	0.06	3	1030	8	<5	<20	78	0.10	<10	98	10	5	44
20	60494	775	0.2	2.35	80	75	<5	5.60	<1	61	31	382	4.97	<10	1.73	1028	2	0.04	6	1060	6	<5	<20	119	0.08	<10	98	20	3	45
21	60495	255	<0.2	2.08	85	80	<5	4.00	<1	35	35	119	4.35	<10	1.48	823	2	0.06	2	1040	6	<5	<20	98	0.10	<10	90	<10	4	43
22	60496	20	<0.2	2.27	45	85	<5	3.01	<1	24	33	70	4.73	<10	1.56	813	2	0.07	3	1070	8	<5	<20	82	0.09	<10	85	<10	5	49
23	60497	115	<0.2	2.15	50	80	<5	4.81	<1	24	35	103	4.55	<10	1.38	890	2	0.05	8	1120	8	<5	<20	83	0.09	<10	87	<10	3	58
24	60498	20	<0.2	4.56	55	55	<5	6.93	<1	41	40	177	8.77	<10	3.79	1708	4	0.04	22	1810	4	<5	<20	111	0.12	<10	213	<10	<1	81
25	60499	15	<0.2	4.02	50	45	<5	8.22	<1	37	55	157	7.98	<10	3.53	1720	7	0.05	24	1580	4	<5	<20	128	0.13	<10	242	<10	<1	64

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK- 97-1038

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	60500	275	0.6	3.83	80	55	<5	>10	<1	42	24	383	7.77	<10	3.15	2110	11	0.04	17	1330	12	<5	<20	195	0.12	<10	208	<10	6	88
27	60501	30	<0.2	3.88	65	65	<5	8.58	<1	38	37	162	8.10	<10	3.47	1424	3	0.05	17	1690	10	<5	<20	138	0.12	<10	280	<10	2	83
28	60502	10	<0.2	3.53	40	60	<5	7.89	<1	38	27	237	7.59	<10	3.18	1430	3	0.05	18	1810	8	<5	<20	170	0.15	<10	291	<10	<1	74
29	60503	25	<0.2	3.04	85	65	<5	5.57	<1	33	13	219	8.77	<10	2.72	1182	4	0.06	4	2000	10	<5	<20	128	0.13	<10	203	<10	4	59
30	60504	35	<0.2	3.70	50	60	<5	8.89	4	35	18	228	7.80	<10	3.19	1374	5	0.05	10	1800	8	<5	<20	151	0.10	<10	229	<10	2	94
31	60505	10	<0.2	2.51	40	75	<5	6.32	<1	25	14	142	5.21	<10	2.20	1148	3	0.08	4	1530	18	<5	<20	130	0.12	<10	184	<10	6	53
32	60506	120	<0.2	4.08	55	80	<5	8.94	2	43	19	285	8.48	<10	3.45	1707	8	0.05	23	1500	12	<5	<20	142	0.15	<10	278	<10	2	150
33	60507	75	<0.2	3.71	65	80	<5	6.20	<1	54	22	284	8.84	<10	3.08	1488	10	0.07	21	1810	12	<5	<20	118	0.13	<10	288	<10	1	95
34	60508	120	0.2	1.98	20	80	<5	5.55	<1	20	29	118	4.83	<10	1.37	998	18	0.08	8	1170	10	<5	<20	115	0.05	<10	116	10	4	85
35	60509	50	0.2	1.79	130	75	<5	5.43	<1	24	26	164	3.97	<10	1.18	995	18	0.07	3	1170	8	<5	<20	114	0.02	<10	103	<10	4	108
36	60510	440	0.8	2.11	1070	65	<5	4.78	<1	73	30	351	4.48	<10	1.42	981	4	0.06	3	1080	8	<5	<20	92	0.03	<10	109	<10	3	129
37	60511	455	0.4	3.94	80	65	<5	5.09	<1	29	20	242	6.69	<10	3.20	1589	7	0.05	18	1500	12	<5	<20	129	0.05	<10	298	10	<1	110
38	60512	55	0.2	3.45	40	65	<5	4.95	<1	21	21	187	7.32	<10	2.89	1418	6	0.06	16	1430	8	<5	<20	114	0.08	<10	239	<10	<1	83
39	60513	75	0.8	2.05	45	80	<5	3.59	<1	25	27	137	4.48	<10	1.41	838	8	0.07	2	1490	12	<5	<20	108	0.03	<10	101	10	2	66
40	60514	90	0.6	1.88	60	70	<5	2.95	1	22	28	193	4.50	<10	1.38	784	13	0.07	<1	1490	10	<5	<20	84	0.02	<10	105	<10	1	98
41	60515	365	0.8	1.99	90	90	<5	5.19	<1	23	30	228	4.40	<10	1.30	1078	10	0.08	2	1320	8	<5	<20	92	0.01	<10	95	<10	1	79
42	60516	360	1.0	1.96	65	90	<5	4.64	<1	28	29	283	4.88	<10	1.35	1043	4	0.06	3	1050	10	<5	<20	88	0.06	<10	108	<10	5	91
43	60517	25	0.2	1.81	30	65	<5	3.24	<1	15	35	108	4.40	<10	1.35	871	5	0.08	2	1040	10	<5	<20	88	0.07	<10	104	20	7	82
44	60518	35	<0.2	2.11	35	65	<5	3.26	<1	18	29	84	4.45	<10	1.38	821	4	0.08	3	1150	10	<5	<20	73	0.07	<10	96	<10	6	88

45	80518	50	<0.2	2.12	40	105	<5	1.83	<1	14	24	69	4.37	<10	1.51	773	8	0.09	1	1540	10	<5	<20	48	0.02	<10	96	<10	1	63
46	80520	45	<0.2	1.86	30	70	<5	3.56	<1	13	22	50	3.84	<10	1.31	763	7	0.10	2	1550	10	<5	<20	77	0.02	<10	96	<10	1	80
47	80521	45	<0.2	1.84	25	85	<5	3.18	<1	14	28	69	4.18	<10	1.37	814	5	0.11	3	1500	10	<5	<20	70	0.02	<10	107	10	2	79
48	80522	60	<0.2	1.84	30	60	<5	3.21	<1	14	23	63	3.80	<10	1.28	814	6	0.10	3	1550	10	<5	<20	83	0.04	<10	90	<10	3	66
49	80523	>1000	1.0	2.84	85	110	<5	3.53	2	35	25	164	6.30	<10	2.04	1315	11	0.05	2	1390	14	<5	<20	84	0.02	<10	106	<10	<1	150
50	80524	85	0.4	1.77	85	85	<5	3.78	<1	20	29	140	4.91	<10	1.11	885	5	0.05	2	1180	16	<5	<20	56	0.07	<10	77	10	6	56
51	80525	55	<0.2	1.54	75	75	<5	3.80	<1	13	34	84	3.42	<10	1.00	758	8	0.11	3	1310	10	<5	<20	79	0.05	<10	109	<10	5	40
52	80526	80	<0.2	1.45	55	65	<5	3.32	<1	12	29	93	3.88	<10	0.94	642	17	0.14	3	1440	10	<5	<20	84	0.04	<10	109	<10	3	38
53	80527	30	<0.2	1.85	15	65	<5	3.07	<1	9	28	81	3.48	<10	1.16	697	10	0.14	2	1810	8	<5	<20	82	0.02	<10	118	<10	3	46
54	80528	40	<0.2	1.72	80	80	<5	3.68	<1	12	25	89	3.70	<10	1.28	801	9	0.11	1	1530	8	<5	<20	58	0.02	<10	117	<10	3	46
55	80529	>1000	2.8	1.92	>10000	75	15	5.00	<1	1783	23	200	8.89	<10	1.35	1057	22	0.02	<1	1020	24	20	<20	86	<0.01	<10	83	30	<1	66
56	80530	>1000	7.0	3.01	>10000	85	<5	4.34	<1	1368	16	888	>10	<10	2.08	1345	31	0.02	3	1230	30	<5	<20	81	0.01	<10	149	<10	<1	115

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-87-1036

ECO-TECH LABORATORIES LTD.

Et#	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
QC/DATA:																															
<i>Repeat:</i>																															
1	80475	130	<0.2	2.32	45	90	<5	6.18	<1	40	42	223	8.16	<10	2.23	1389	2	0.08	14	1480	<2	<5	<20	77	0.15	<10	210	<10	<1	55	
38	80510	485	0.8	2.07	1020	70	<5	4.88	<1	70	30	372	4.57	<10	1.44	1001	4	0.05	2	1090	10	<5	<20	94	0.02	<10	108	10	3	138	
<i>Repeat:</i>																															
1	80475	120	<0.2	2.37	35	90	<5	6.37	<1	41	44	232	8.15	<10	2.29	1414	3	0.08	16	1480	<2	<5	<20	79	0.14	<10	210	<10	<1	58	
10	80484	25	<0.2	3.63	40	65	<5	4.67	<1	28	54	122	8.79	<10	4.02	1228	1	0.05	17	1670	4	<5	<20	84	0.19	<10	248	<10	<1	45	
19	80493	455	<0.2	2.01	70	85	<5	4.00	<1	44	31	128	4.32	<10	1.41	846	<1	0.05	2	1020	6	<5	<20	75	0.10	<10	97	<10	6	44	
36	80510	450	0.8	2.13	1085	80	<5	4.81	<1	74	30	362	4.53	<10	1.44	994	5	0.06	2	1090	10	<5	<20	91	0.02	<10	110	10	3	132	
45	80519	45	0.2	2.17	45	115	<5	1.85	<1	14	25	89	4.44	<10	1.52	781	6	0.09	2	1590	12	<5	<20	48	0.02	<10	96	10	1	65	
<i>Standard:</i>																															
GEO'97		140	1.2	1.70	60	155	<5	1.70	<1	19	58	77	3.94	<10	0.92	658	<1	0.03	24	830	22	<5	<20	57	0.11	<10	75	<10	4	65	
GEO'97		160	1.4	1.78	60	155	<5	1.78	<1	21	60	81	4.13	<10	0.96	684	<1	0.03	22	690	22	<5	<20	58	0.11	<10	78	<10	5	70	

dfl/1027
 XLS/97Teuton
 Fax to Dino Vancouver 604-682-3982

ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

CERTIFICATE OF ASSAY AK 97-1036

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

25-Sep-97

ATTENTION: DINO CREMONESE

No. of samples received: 56

Sample type: CORE

PROJECT: # CLONE

SHIPMENT: # CL-12

Samples submitted by: DALE ROBERTS

ET #.	Tag #	Au (g/t)	Au (oz/t)	As (%)	Co (%)
12	60486	12.20	0.356	-	0.119
17	60491	1.24	0.036	-	0.029
18	60492	1.45	0.042	-	-
49	60523	1.99	0.058	-	-
55	60529	10.48	0.306	4.76	0.210
56	60530	21.00	0.612	1.05	0.158

QC/DATA:

Standard:

STD-M	1.42	0.041	-	-
CD-1	-	-	0.66	-
MP-1a	-	-	-	0.041

XLS/97Teuton

Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

CERTIFICATE OF ASSAY AK 97 - 1041

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

1-Oct-97

ATTENTION: DINO CREMONESE

No. of samples received: 117

Sample Type: Core

PROJECT #: Clone

SHIPMENT #: 14

P.O.#: Not Given

Samples submitted by: Dale Roberts

ET #.	Tag #	Au (g/t)	Au (oz/t)	As (%)	Co (%)
6	60569	1.12	0.033	-	0.052
40	61753	1.39	0.041	-	-
42	61755	-	-	-	0.030
43	61756	-	-	-	0.030
69	61782	1.47	0.043	-	-
70	61783	2.57	0.075	-	-
91	61804	6.98	0.204	1.88	-
111	61824	1.66	0.048	-	-
113	61826	5.13	0.150	-	-
115	61828	1.12	0.033	-	-

QC/DATA:

Standard:

Su-1a	-	-	-	-	0.041
CD-1	-	-	0.70	-	-

XLS/97Teuton
Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

30-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK-97-1041

TELTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 117

Sample Type: Core

PROJECT #: Clone

SHIPMENT #: CI - 14

P.O.#: Not Given

Samples submitted by: Dale Roberts

Values in ppm unless otherwise reported

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	80564	15	<0.2	3.70	15	50	<5	3.92	<1	21	8	92	8.28	<10	3.04	1345	3	0.02	2	2190	<2	<5	<20	142	0.10	<10	213	<10	<1	75
2	80565	50	<0.2	3.49	30	45	<5	3.10	1	38	9	238	9.55	<10	2.54	1397	3	0.02	5	2200	10	<5	<20	105	0.08	<10	268	20	<1	112
3	80566	25	<0.2	3.29	50	45	<5	3.56	<1	38	9	237	8.97	<10	2.42	1415	4	0.02	2	1890	12	<5	<20	118	0.08	<10	249	10	<1	125
4	80567	40	<0.2	3.48	60	40	<5	3.88	<1	39	41	271	8.99	<10	2.81	1295	6	0.02	12	1930	10	<5	<20	141	0.09	<10	271	<10	<1	108
5	80568	10	<0.2	4.26	65	35	<5	5.48	<1	41	36	144	6.40	<10	3.98	1812	8	0.02	12	1770	4	<5	<20	232	0.05	<10	307	<10	2	143
6	80569	>1000	<0.2	4.32	750	35	<5	4.84	<1	520	13	184	8.76	<10	4.22	1502	5	0.03	11	1720	4	<5	<20	160	0.09	<10	301	<10	1	100
7	80570	60	<0.2	4.20	115	40	<5	4.16	<1	52	25	145	8.18	<10	4.26	1381	9	0.03	11	1850	8	<5	<20	141	0.17	<10	299	<10	3	90
8	80571	70	<0.2	3.87	115	40	<5	4.48	<1	48	20	137	7.48	<10	4.00	1353	28	0.04	9	1790	8	<5	<20	170	0.11	<10	288	<10	4	85
9	80572	35	<0.2	4.11	180	40	<5	4.87	<1	44	29	127	7.82	<10	4.14	1434	88	0.03	11	1900	8	5	<20	129	0.17	<10	312	<10	4	70
10	80573	5	<0.2	1.84	10	70	<5	1.97	<1	10	12	47	4.02	<10	1.35	867	1	0.03	2	1530	28	5	<20	41	0.08	<10	65	<10	<1	175
11	80574	5	<0.2	1.86	10	65	<5	1.80	<1	9	23	31	3.88	<10	1.37	962	1	0.03	2	1510	14	<5	<20	50	0.07	<10	65	20	<1	133
12	80575	65	0.4	1.86	20	95	<5	1.88	<1	10	19	281	3.52	<10	1.28	801	<1	0.03	2	1550	20	15	<20	50	0.07	<10	63	<10	1	81
13	80576	5	<0.2	1.31	15	80	<5	2.34	<1	10	27	30	3.43	<10	1.00	888	<1	0.04	1	1580	44	<5	<20	55	0.07	<10	68	<10	3	119
14	80577	35	<0.2	1.18	15	200	5	3.13	1	10	18	24	3.91	<10	0.82	764	2	0.03	3	1510	48	5	<20	61	0.07	<10	71	<10	3	211
15	80578	15	<0.2	1.38	15	65	5	1.84	<1	10	25	14	3.06	<10	1.07	708	1	0.04	2	1530	12	<5	<20	44	0.08	<10	58	20	2	118
16	80579	20	<0.2	1.24	20	85	<5	1.92	<1	11	20	188	3.26	<10	0.94	837	<1	0.04	1	1520	18	10	<20	42	0.08	<10	78	<10	3	88
17	80580	10	<0.2	0.90	10	70	<5	2.77	<1	9	26	15	2.86	<10	0.83	812	<1	0.04	3	1520	12	<5	<20	51	0.07	<10	62	10	4	41
18	80581	125	<0.2	0.94	25	60	<5	2.56	<1	17	19	23	3.57	<10	0.80	587	<1	0.03	4	1550	24	<5	<20	41	0.07	<10	65	40	4	45
19	80582	5	<0.2	1.23	20	80	<5	2.75	<1	10	24	20	3.55	<10	0.81	716	1	0.03	1	1520	16	<5	<20	46	0.07	<10	67	10	3	89
20	80583	75	<0.2	1.05	15	85	5	2.82	<1	14	27	13	3.42	<10	0.85	565	<1	0.04	2	1560	12	<5	<20	52	0.08	<10	63	10	3	37
21	80584	55	<0.2	3.72	35	65	<5	2.39	2	92	22	242	7.84	<10	3.58	1360	2	0.02	14	2010	10	<5	<20	38	0.08	<10	118	<10	1	287
22	80585	5	<0.2	4.10	35	55	<5	3.28	<1	51	6	252	7.25	<10	4.13	1347	<1	0.02	5	1840	8	5	<20	49	0.19	<10	179	<10	5	140
23	80586	5	<0.2	4.12	35	45	<5	6.81	<1	39	51	142	7.53	<10	4.09	1578	<1	0.02	13	1730	8	10	<20	79	0.19	<10	203	<10	2	81
24	80587	5	<0.2	4.34	60	40	5	4.44	<1	45	28	148	9.53	<10	4.33	1432	2	0.03	18	2210	18	<5	<20	66	0.17	<10	287	120	2	78
25	80588	25	<0.2	3.89	35	45	<5	5.44	<1	39	23	228	9.71	<10	3.61	1476	2	0.03	13	2160	2	<5	<20	64	0.17	<10	230	30	<1	88

TELTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1041

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	80589	10	<0.2	4.65	40	35	<5	5.19	<1	45	80	141	8.95	<10	4.47	1825	<1	0.03	17	1860	6	<5	<20	58	0.19	<10	272	<10	<1	70
27	80590	5	<0.2	4.82	35	45	5	5.26	<1	40	77	80	8.89	<10	4.51	1747	<1	0.03	18	1890	2	<5	<20	78	0.20	<10	258	<10	<1	88
28	80591	5	0.4	4.47	20	45	<5	8.33	10	43	83	101	8.81	<10	4.52	1788	3	0.03	18	1810	<2	<5	<20	100	0.08	<10	287	<10	<1	88
29	80592	220	<0.2	3.18	120	60	<5	2.14	1	85	34	729	>10	<10	2.89	1081	8	0.02	20	2060	8	<5	<20	44	0.12	<10	170	<10	<1	201
30	80593	50	0.4	3.35	60	55	<5	5.90	7	39	30	211	7.59	<10	3.07	1472	6	0.03	13	1870	10	<5	<20	95	0.08	<10	208	<10	<1	87
31	80594	15	0.4	3.45	60	60	<5	5.10	8	50	38	254	9.06	<10	3.10	1783	2	0.03	21	1850	8	<5	<20	63	0.10	<10	258	<10	<1	102
32	80595	40	0.6	3.90	35	50	<5	3.48	11	60	42	297	9.48	<10	3.88	1768	2	0.02	18	1570	<2	<5	<20	53	0.07	<10	243	<10	<1	109
33	80596	5	0.4	3.59	35	60	<5	5.73	8	42	38	182	7.84	<10	3.51	1797	2	0.03	18	1580	<2	<5	<20	74	0.09	<10	227	<10	<1	88
34	80597	150	0.4	3.10	55	105	<5	7.38	8	43	52	290	7.52	<10	3.23	1546	1	0.03	15	1510	<2	<5	<20	126	0.06	<10	226	<10	<1	78
35	80598	5	0.4	2.85	40	390	<5	3.98	7	32	51	112	5.80	<10	3.43	1141	1	0.07	18	1850	<2	<5	<20	78	0.07	<10	188	<10	<1	48
36	80599	5	<0.2	2.83	30	80	<5	2.81	<1	28	48	119	5.78	<10	3.45	1050	1	0.07	18	1710	<2	5	<20	47	0.14	<10	144	<10	<1	48
37	80600	5	<0.2	3.02	45	35	<5	3.48	<1	32	51	502	8.94	<10	3.67	1192	<1	0.08	17	1730	8	<5	<20	48	0.19	<10	174	30	<1	85
38	81751	150	<0.2	3.27	80	45	<5	2.86	<1	84	80	281	>10	<10	3.97	1272	3	0.04	22	1480	4	<5	<20	40	0.18	<10	191	<10	<1	129
39	81752	510	<0.2	2.87	105	50	<5	4.45	<1	74	75	338	>10	<10	3.43	1172	3	0.03	22	1540	8	<5	<20	58	0.18	<10	212	80	<1	108
40	81753	>1000	<0.2	3.83	55	40	<5	4.70	<1	63	84	498	>10	<10	4.32	1388	<1	0.02	16	1590	4	<5	<20	71	0.22	<10	259	<10	<1	102
41	81754	35	<0.2	3.33	50	40	10	4.87	<1	28	54	119	8.82	<10	3.64	1218	<1	0.03	16	1740	4	<5	<20	74	0.24	<10	288	20	<1	58

42	61755	>1000	0.6	2.50	400	90	10	3.81	<1	276	46	118	>10	<10	2.57	896	5	0.02	10	1610	6	<5	<20	57	0.17	<10	228	80	<1	83
43	61756	430	<0.2	4.01	400	40	<5	4.15	<1	289	27	758	8.83	<10	4.08	1234	<1	0.03	13	1900	6	<5	<20	56	0.21	<10	249	40	3	61
44	61757	5	<0.2	4.18	80	100	<5	8.31	<1	43	41	182	8.98	<10	4.27	1412	<1	0.03	26	1750	<2	<5	<20	101	0.20	<10	264	10	<1	48
45	61758	15	<0.2	4.24	65	50	<5	7.93	<1	36	27	125	9.40	<10	3.83	1053	2	0.03	23	1550	4	<5	<20	120	0.20	<10	284	20	<1	57
46	61759	235	<0.2	2.83	150	40	<5	5.58	<1	89	7	329	7.03	<10	2.28	1163	25	0.03	4	2020	8	<5	<20	86	0.14	<10	178	10	6	45
47	61760	25	<0.2	2.87	100	40	<5	4.47	<1	32	8	312	8.79	<10	2.42	1070	18	0.03	2	2120	12	<5	<20	84	0.17	<10	184	20	9	45
48	61761	5	<0.2	2.85	115	45	<5	5.57	<1	35	10	324	7.27	<10	2.73	1354	6	0.04	3	2040	12	<5	<20	115	0.19	<10	221	<10	7	49
49	61762	50	<0.2	2.71	155	30	<5	5.95	<1	31	16	156	8.55	<10	2.32	1278	6	0.04	5	1890	12	<5	<20	120	0.14	<10	200	10	6	58
50	61763	40	<0.2	2.12	85	30	<5	4.24	<1	20	36	45	4.83	<10	1.74	985	<1	0.04	2	1120	10	<5	<20	88	0.13	<10	120	<10	7	48
51	61764	10	<0.2	2.09	40	35	<5	4.01	<1	18	30	58	4.48	<10	1.85	901	1	0.03	2	1110	12	<5	<20	98	0.13	<10	89	30	6	47
52	61765	30	<0.2	2.50	95	35	<5	4.70	<1	31	36	208	8.01	<10	2.11	1065	14	0.04	9	1430	14	<5	<20	105	0.16	<10	170	20	6	55
53	61768	85	<0.2	3.74	95	40	<5	>10	<1	48	38	280	8.86	<10	3.29	2149	15	0.03	19	1650	18	<5	<20	169	0.22	<10	247	20	6	82
54	61767	75	<0.2	4.33	80	40	10	7.82	<1	32	84	123	9.28	<10	4.08	1787	10	0.02	14	1780	14	<5	<20	129	0.21	<10	284	20	<1	90
55	61768	30	<0.2	4.35	65	115	<5	7.04	<1	23	23	127	7.84	<10	4.58	1583	4	0.03	13	1780	12	<5	<20	136	0.21	<10	286	40	4	68
58	61769	35	<0.2	4.07	75	95	<5	6.87	<1	22	21	152	7.70	<10	4.32	1511	9	0.04	13	1850	16	15	<20	141	0.19	<10	267	40	3	65
57	61770	80	<0.2	3.76	90	45	<5	4.98	<1	37	23	380	8.45	<10	4.24	1469	9	0.04	16	1750	20	<5	<20	140	0.19	<10	258	40	<1	75
58	61771	30	<0.2	3.85	60	75	<5	6.18	<1	28	57	197	8.40	<10	3.77	1435	10	0.04	13	1640	20	<5	<20	120	0.20	<10	281	40	3	70
59	61772	40	<0.2	4.16	75	40	5	8.20	<1	34	20	180	8.50	<10	4.38	1423	3	0.03	13	1860	20	<5	<20	107	0.22	<10	288	40	5	70
60	61773	70	<0.2	4.37	105	50	<5	4.83	<1	35	40	178	8.80	<10	4.58	1459	4	0.03	12	1970	20	<5	<20	88	0.19	<10	285	40	4	73

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1041

ECO-TECH LABORATORIES LTD.

El #.	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
61	61774	65	<0.2	3.44	105	60	<5	8.82	<1	35	42	177	7.38	<10	3.52	1374	<1	0.04	7	1620	18	10	<20	178	0.22	<10	232	40	5	79
62	61775	45	<0.2	4.14	75	45	<5	5.77	<1	35	23	130	8.92	<10	4.08	1303	3	0.03	11	1840	22	<5	<20	111	0.19	<10	273	30	2	81
63	61776	200	<0.2	3.39	80	40	<5	7.46	<1	27	32	245	7.44	<10	3.25	1370	5	0.03	11	1850	16	<5	<20	138	0.18	<10	265	60	5	78
64	61777	210	<0.2	4.48	85	45	<5	8.10	<1	39	29	282	9.95	<10	4.28	1694	2	0.02	20	2180	22	<5	<20	141	0.18	<10	338	30	3	121
65	61778	30	<0.2	4.10	90	50	<5	7.53	<1	50	28	347	>10	<10	3.83	1727	5	0.03	19	1990	24	<5	<20	142	0.18	<10	288	30	<1	86
68	61779	5	<0.2	3.87	80	35	<5	7.81	<1	42	35	286	8.66	<10	3.88	1614	6	0.02	14	1940	22	<5	<20	143	0.13	<10	251	80	<1	82
67	61780	55	<0.2	2.78	100	35	<5	8.12	<1	34	20	278	8.73	<10	2.47	1228	5	0.03	7	1630	18	<5	<20	97	0.13	<10	165	<10	4	93
66	61781	25	0.4	2.25	45	35	<5	6.90	5	25	30	138	4.84	<10	1.80	1418	8	0.04	7	1580	34	10	<20	103	0.08	<10	110	30	11	105
69	61782	>1000	1.6	3.19	440	80	<5	4.74	<1	95	30	733	7.24	<10	2.43	1471	5	0.03	4	1950	20	<5	<20	114	0.05	<10	189	<10	3	181
70	61783	>1000	2.0	3.52	875	50	<5	7.31	<1	138	22	889	7.71	<10	2.83	1591	5	0.01	6	1860	28	<5	<20	123	0.11	<10	259	30	2	158
71	61784	260	0.6	3.79	190	50	<5	7.41	<1	67	20	371	8.01	<10	3.58	1690	3	0.03	11	1590	14	<5	<20	125	0.19	<10	327	<10	<1	180
72	61785	825	<0.2	4.03	80	45	<5	5.14	<1	41	18	243	9.87	<10	3.81	1547	<1	0.03	9	1970	20	<5	<20	85	0.21	<10	296	<10	<1	173
73	61786	5	<0.2	3.37	115	55	<5	5.24	<1	37	15	145	7.48	<10	3.32	1281	3	0.04	13	1820	12	<5	<20	81	0.20	<10	230	40	2	86
74	61787	5	<0.2	2.98	180	60	<5	5.25	<1	38	17	177	6.87	<10	2.74	1180	6	0.04	13	1780	14	<5	<20	98	0.19	<10	180	20	3	59
75	61788	10	<0.2	3.30	115	60	<5	4.29	<1	44	21	157	7.83	<10	3.03	1420	3	0.04	15	1970	18	<5	<20	112	0.23	<10	219	<10	1	134
76	61789	5	<0.2	3.20	100	60	<5	3.13	<1	44	22	180	7.88	<10	2.87	1371	4	0.04	15	1890	22	<5	<20	74	0.20	<10	209	40	1	105
77	61790	20	<0.2	3.07	125	50	<5	3.32	<1	39	16	134	7.41	<10	2.81	1282	2	0.04	13	1860	18	<5	<20	67	0.18	<10	190	<10	<1	124
78	61791	5	<0.2	2.70	115	40	<5	3.48	<1	42	18	218	7.04	<10	2.44	1107	4	0.03	15	1990	18	<5	<20	72	0.17	<10	159	<10	<1	78
79	61792	5	<0.2	3.65	90	45	<5	3.87	<1	44	20	172	8.41	<10	3.39	1597	4	0.03	18	2180	18	<5	<20	98	0.17	<10	193	30	<1	102
80	61793	50	<0.2	3.83	110	55	<5	5.00	<1	48	20	186	8.70	<10	3.18	1641	5	0.04	15	1970	20	<5	<20	88	0.20	<10	247	40	<1	101
81	61794	65	<0.2	3.43	115	55	<5	4.89	<1	39	13	127	8.23	<10	3.13	1578	2	0.04	11	2010	18	<5	<20	89	0.19	<10	242	<10	<1	90
82	61795	45	<0.2	3.48	180	90	<5	4.08	<1	48	22	182	8.60	<10	3.19	1631	2	0.04	16	2010	22	<5	<20	95	0.19	<10	250	<10	<1	89
83	61796	25	<0.2	4.01	190	115	<5	2.88	<1	53	17	190	9.72	<10	3.68	1796	1	0.04	16	2050	26	<5	<20	74	0.18	<10	289	70	2	89
84	61797	50	<0.2	4.00	185	95	<5	2.68	<1	43	20	144	9.17	<10	3.88	1708	2	0.03	11	2180	24	<5	<20	63	0.18	<10	284	20	2	90
85	61798	55	<0.2	3.73	180	60	<5	7.58	<1	42	12	188	8.87	<10	3.50	2247	1	0.03	11	1980	20	<5	<20	106	0.20	<10	307	40	11	71
86	61799	20	<0.2	4.14	100	50	<5	8.37	<1	38	12	145	9.52	<10	3.92	1944	<1	0.03	11	2030	18	<5	<20	117	0.18	<10	322	40	4	84
87	61800	30	<0.2	3.48	75	50	<5	7.29	<1	33	21	118	8.00	<10	3.25	1703	1	0.04	9	2150	18	<5	<20	108	0.15	<10	255	10	4	82
88	61801	10	<0.2	3.65	140	45	<5	4.88	<1	41	22	153	8.48	<10	3.80	1490	2	0.03	11	2200	22	<5	<20</							

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1041

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
96	61809	10	<0.2	4.15	100	65	5	6.12	<1	36	18	124	9.50	<10	3.85	1771	8	0.04	15	1990	28	<5	<20	119	0.20	<10	312	30	1	94
97	61810	25	<0.2	3.74	70	35	<5	7.87	<1	35	18	110	8.54	<10	3.59	1755	3	0.03	10	1950	22	<5	<20	151	0.14	<10	263	10	<1	89
98	61811	15	<0.2	3.62	45	40	10	3.69	<1	33	5	99	7.51	<10	3.88	1518	1	0.03	4	2290	24	5	<20	97	0.13	<10	258	<10	2	142
99	61812	15	<0.2	4.21	75	40	5	5.55	<1	39	15	89	8.50	<10	4.09	1778	2	0.03	14	2090	22	<5	<20	184	0.14	<10	283	<10	3	224
100	61813	10	<0.2	4.05	60	35	<5	6.74	<1	41	24	145	8.40	<10	3.99	1921	3	0.03	11	1930	20	<5	<20	149	0.11	<10	287	20	2	167
101	61814	35	<0.2	3.80	80	40	<5	5.86	<1	42	12	178	8.33	<10	3.91	1870	8	0.03	7	2170	30	10	<20	139	0.12	<10	285	<10	3	169
102	61815	45	<0.2	4.09	215	30	<5	7.06	<1	39	12	139	8.29	<10	4.21	2132	4	0.02	8	1940	30	10	<20	190	0.09	<10	265	10	3	159
103	61816	90	<0.2	4.54	395	25	<5	7.12	<1	36	32	124	8.95	<10	4.38	1777	10	0.03	14	2090	30	<5	<20	271	0.08	<10	298	50	<1	120
104	61817	45	<0.2	3.75	85	35	<5	5.21	<1	34	13	148	7.83	<10	3.84	1565	32	0.03	8	2340	32	<5	<20	114	0.12	<10	263	<10	3	140
105	61818	50	<0.2	3.37	125	40	<5	4.68	<1	48	12	141	7.89	<10	3.12	1238	24	0.03	3	2590	28	<5	<20	117	0.10	<10	228	30	4	84
106	61819	50	<0.2	3.69	50	50	<5	3.87	<1	34	25	178	7.82	<10	3.69	1179	5	0.03	8	1860	4	<5	<20	88	0.14	<10	259	<10	2	58
107	61820	10	<0.2	3.87	80	40	<5	6.15	<1	37	36	130	7.99	<10	3.84	1574	18	0.03	12	1830	10	<5	<20	126	0.13	<10	274	<10	2	80
108	61821	5	<0.2	3.79	80	40	<5	8.91	<1	35	41	118	7.55	<10	3.70	1807	4	0.02	14	1720	2	<5	<20	204	0.10	<10	278	<10	2	83
109	61822	15	<0.2	4.03	30	85	<5	3.96	<1	28	14	137	8.27	<10	3.25	1090	4	0.02	8	2010	10	<5	<20	76	0.04	<10	137	<10	5	66
110	61823	15	<0.2	3.47	20	85	<5	5.92	<1	24	13	152	7.70	<10	2.88	1298	5	0.02	8	1910	10	<5	<20	128	0.03	<10	130	<10	3	80
111	61824	>1000	1.6	2.79	130	130	<5	1.27	<1	41	14	1018	7.33	<10	2.02	771	8	0.02	8	1710	18	<5	<20	31	0.01	<10	97	<10	<1	125
112	61825	455	0.8	2.75	75	185	<5	1.18	<1	35	17	523	8.29	<10	2.00	889	4	0.01	4	1780	12	<5	<20	30	0.02	<10	82	<10	<1	101
113	61826	>1000	2.6	2.24	205	85	<5	0.78	<1	66	13	673	5.31	<10	1.55	635	5	0.02	<1	1440	10	<5	<20	18	<0.01	<10	59	<10	<1	132
114	61827	215	0.2	2.17	20	75	<5	1.45	<1	13	14	185	4.33	<10	1.80	730	3	0.02	<1	1500	8	<5	<20	28	<0.01	<10	47	<10	<1	108
115	61828	>1000	0.4	1.95	25	100	<5	1.87	<1	9	17	120	3.79	<10	1.44	785	2	0.02	<1	1550	8	<5	<20	30	<0.01	<10	49	<10	<1	98
116	61829	380	0.6	1.91	100	115	<5	0.95	<1	14	16	310	4.18	<10	1.38	716	3	0.02	<1	1530	12	<5	<20	17	0.03	<10	47	20	1	111
117	61830	45	1.0	1.47	395	55	<5	1.53	<1	22	23	215	5.63	<10	0.92	848	8	0.02	1	1050	16	<5	<20	30	0.04	<10	30	<10	<1	84

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1041

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
QC/DATA:																															
<i>Resplit:</i>																															
R/S 1	60564	15	<0.2	3.81	25	65	<5	4.00	<1	21	6	88	8.63	<10	3.17	1388	2	0.03	2	2290	<2	<5	<20	145	0.04	<10	222	<10	<1	79	
R/S 36	60599	5	<0.2	2.87	50	75	10	2.87	<1	31	49	115	6.07	<10	3.49	1067	<1	0.06	18	1850	14	15	<20	44	0.19	<10	159	70	2	48	
R/S 71	61784	285	0.4	3.71	215	45	<5	7.71	<1	72	26	354	8.48	<10	3.50	1739	3	0.03	11	1620	20	<5	<20	118	0.20	<10	321	30	2	183	
R/S 108	61819	30	<0.2	3.52	55	40	<5	3.82	<1	34	24	174	7.59	<10	3.52	1152	8	0.03	8	1870	4	<5	<20	90	0.13	<10	248	<10	3	57	
<i>Repeat:</i>																															
1	60564	20	<0.2	3.78	25	40	<5	4.02	<1	22	9	93	8.43	<10	3.11	1375	4	0.02	2	2310	8	<5	<20	141	0.11	<10	218	<10	1	77	
10	60573	5	<0.2	1.83	15	75	<5	1.97	<1	10	12	48	4.02	<10	1.32	983	<1	0.03	2	1530	28	10	<20	41	0.07	<10	65	<10	<1	176	
19	60582	5	<0.2	1.31	15	70	<5	2.89	4	11	26	21	3.78	<10	0.87	748	<1	0.03	1	1800	14	<5	<20	51	0.03	<10	72	<10	3	73	
36	60599	5	<0.2	2.91	35	80	<5	2.71	<1	30	48	122	5.94	<10	3.55	1074	<1	0.06	18	1750	4	10	<20	47	0.16	<10	153	20	1	44	
45	61758	10	<0.2	4.22	65	50	5	8.03	<1	36	28	125	9.48	<10	3.79	1863	2	0.03	26	1820	8	<5	<20	121	0.21	<10	266	50	2	58	

54	81787	75	<0.2	4.51	90	40	<5	7.80	<1	32	52	123	9.41	<10	4.04	1808	7	0.02	14	1850	24	<5	<20	127	0.22	<10	288	<10	2	98	
71	81784	255	0.2	3.86	210	45	<5	7.65	<1	70	21	369	8.41	<10	3.63	1757	3	0.03	12	1730	26	<5	<20	122	0.19	<10	332	<10	1	177	
80	81793	40	<0.2	3.52	100	50	<5	4.82	<1	48	20	181	8.81	<10	3.12	1818	4	0.04	15	1850	22	<5	<20	82	0.18	<10	238	<10	<1	101	
89	81802	30	<0.2	3.80	115	40	<5	6.37	<1	39	18	174	8.89	<10	3.38	1594	4	0.04	12	2110	24	<5	<20	87	0.15	<10	265	<10	1	85	
108	81819	80	<0.2	3.64	80	45	<5	3.80	<1	34	24	176	7.88	<10	3.63	1182	4	0.03	7	1880	4	<5	<20	92	0.15	<10	255	<10	3	57	
Standard:																															
GEO'97		185	1.4	1.82	75	170	<5	1.80	<1	17	59	79	4.10	<10	1.01	692	<1	0.03	22	880	20	<5	<20	77	0.03	<10	84	<10	<1	70	
GEO'97		155	1.2	1.88	75	150	<5	1.85	<1	21	61	88	4.20	<10	1.01	712	<1	0.03	25	710	22	<5	<20	60	0.13	<10	84	20	5	75	
GEO'97		165	1.2	1.70	70	150	<5	1.85	<1	21	59	80	4.18	<10	0.96	702	<1	0.03	22	740	22	<5	<20	55	0.11	<10	80	<10	4	83	
GEO'97		-	1.4	1.74	55	145	<5	1.87	<1	19	62	80	4.00	<10	0.93	654	<1	0.03	23	840	22	<5	<20	59	0.12	<10	77	10	4	68	

df/1040
XLS/87Tauton
Fax to Dino Vancouver 604-682-3982

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AK 97-1042

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

26-Sep-97

ATTENTION: DINO CREMONESE

No. of samples received: 40

Sample type: CORE

PROJECT: # CLONE

SHIPMENT: # CL-12

Samples submitted by: DALE ROBERTS

ET #.	Tag #	Au (g/t)	Au (oz/t)
11	60216	2.57	0.075

XLS/97Teuton
Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

26-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK-97-1042

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 42
Sample type: CORE
PROJECT: # CLONE
SHIPMENT: # CL-12
Samples submitted by: DALE ROBERTS

Values in ppm unless otherwise reported

Et#	Tag#	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	80198	5	<0.2	1.58	10	90	<5	3.04	<1	8	38	35	3.09	<10	0.93	836	2	0.08	3	1530	10	<5	<20	64	0.02	<10	88	<10	1	62
2	80200	15	<0.2	1.58	15	75	5	4.18	<1	10	26	30	3.03	<10	0.97	771	2	0.08	2	1530	4	<5	<20	79	0.03	<10	68	10	2	57
3	80201	5	<0.2	1.83	10	135	5	4.64	<1	10	24	32	3.85	<10	1.04	855	2	0.08	3	1530	8	<5	<20	84	0.02	<10	77	<10	2	57
4	80202	5	<0.2	1.93	10	85	<5	3.67	<1	10	25	43	3.74	<10	1.19	769	3	0.07	2	1520	4	<5	<20	63	0.02	<10	68	<10	<1	62
5	80203	190	0.6	2.12	70	95	<5	2.24	<1	22	22	171	4.29	<10	1.33	869	3	0.04	2	1570	32	<5	<20	47	0.02	<10	87	<10	<1	71
6	80204	10	<0.2	2.19	60	110	<5	1.72	<1	12	21	30	3.93	<10	1.39	599	3	0.05	2	1570	6	<5	<20	46	0.01	<10	54	<10	<1	42
7	80205	10	<0.2	2.05	40	105	5	2.18	<1	11	22	30	4.03	<10	1.41	637	2	0.05	2	1540	2	<5	<20	59	0.02	<10	59	<10	<1	39
8	80213	15	<0.2	1.87	20	80	<5	2.74	<1	9	26	99	3.96	<10	1.44	797	2	0.08	2	1510	8	<5	<20	85	0.05	<10	106	<10	2	68
9	80214	10	0.4	1.89	45	80	<5	3.86	2	12	26	172	4.05	<10	1.25	984	3	0.08	2	1440	20	<5	<20	79	0.03	<10	99	<10	2	236
10	80215	35	0.4	1.75	25	60	<5	5.16	<1	12	26	121	4.14	<10	1.18	1217	3	0.07	3	1430	20	<5	<20	100	0.02	<10	86	10	1	82
11	80216	>1000	3.6	3.05	935	80	<5	7.76	8	65	24	535	8.60	<10	2.00	2183	10	0.02	5	1250	574	<5	<20	151	0.03	<10	125	<10	<1	1299
12	80217	20	0.4	4.80	30	65	<5	8.91	<1	34	44	195	>10	<10	3.72	2313	5	0.04	17	1500	2	<5	<20	215	0.07	<10	288	<10	<1	133
13	80218	40	0.4	3.87	40	50	<5	>10	<1	39	41	183	8.41	<10	3.23	1999	8	0.06	19	1550	8	<5	<20	233	0.07	<10	255	10	<1	74
14	80219	15	<0.2	3.54	30	55	<5	4.97	<1	30	20	176	7.39	<10	3.39	1465	7	0.04	5	1780	4	<5	<20	183	0.08	<10	234	10	3	70
15	80220	25	<0.2	4.29	25	55	<5	4.61	<1	37	12	135	9.07	<10	3.99	1575	7	0.04	9	1850	4	<5	<20	110	0.08	<10	272	<10	2	83
16	80221	40	0.4	3.86	30	70	<5	5.71	<1	31	15	145	8.82	<10	3.24	1685	10	0.03	7	1650	6	<5	<20	132	0.08	<10	242	<10	3	80
17	80222	20	0.4	3.80	25	60	<5	5.39	<1	30	6	145	8.78	<10	3.05	1709	9	0.03	5	1720	6	<5	<20	171	0.08	<10	245	<10	3	83
18	80223	10	0.6	2.76	40	60	<5	5.88	<1	30	24	150	7.06	<10	2.13	1427	11	0.04	6	1290	10	<5	<20	139	0.03	<10	202	<10	<1	75
19	80224	30	0.6	4.48	30	60	5	5.10	<1	36	7	161	9.85	<10	3.64	1774	12	0.04	5	1640	4	<5	<20	125	0.03	<10	277	10	<1	89
20	80225	35	0.4	4.22	35	60	<5	5.61	13	34	10	141	9.28	<10	3.38	1809	10	0.04	7	1830	60	<5	<20	142	0.03	<10	272	<10	3	395
21	80226	15	0.8	4.17	45	60	<5	8.85	<1	34	6	133	6.50	<10	3.51	2104	22	0.04	5	1880	4	<5	<20	175	0.03	<10	242	<10	5	97
22	80234	20	0.2	2.67	150	115	<5	9.01	<1	25	25	86	6.87	<10	1.64	1443	6	0.02	5	980	8	<5	<20	292	0.01	<10	96	10	<1	47
23	80235	15	0.6	2.86	100	125	<5	9.66	3	28	29	88	7.23	<10	1.41	1704	9	0.01	8	1010	54	5	<20	235	0.01	<10	74	10	<1	202
24	80236	30	0.4	3.37	70	110	<5	5.74	2	29	32	116	7.90	<10	2.24	1460	6	0.03	6	1050	16	<5	<20	139	0.01	<10	111	10	<1	169
25	80237	25	0.4	2.98	95	110	<5	5.41	<1	22	29	122	7.92	<10	2.10	1299	7	0.04	7	1170	10	<5	<20	177	0.01	<10	118	10	<1	62

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1042

ECO-TECH LABORATORIES LTD.

Et#	Tag#	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
26	80238	25	0.8	1.87	20	80	15	1.21	<1	12	26	115	4.58	<10	1.06	1021	<1	0.06	2	1700	22	<5	<20	41	0.08	<10	87	10	2	88
27	80239	25	<0.2	1.53	15	95	15	1.14	<1	12	21	23	5.07	<10	0.98	982	2	0.08	2	1780	12	<5	<20	39	0.08	<10	74	10	<1	114
28	80240	10	<0.2	1.21	20	90	10	1.58	<1	9	38	12	4.63	<10	0.73	792	2	0.06	4	1620	12	<5	<20	53	0.07	<10	78	10	<1	73
29	80241	190	<0.2	1.70	15	125	10	1.06	<1	29	33	31	4.05	<10	1.04	614	<1	0.04	3	1580	14	<5	<20	121	0.08	<10	71	<10	<1	97
30	80242	95	<0.2	1.82	15	120	5	0.90	<1	23	27	46	4.83	<10	1.29	680	1	0.63	2	1690	14	<5	<20	31	0.07	<10	85	<10	<1	89
31	80243	20	<0.2	1.81	10	95	10	0.96	<1	14	22	12	4.71	<10	1.32	806	<1	0.04	3	1700	12	<5	<20	38	0.09	<10	68	10	<1	91
32	80244	5	<0.2	1.38	5	125	<5	1.52	<1	12	24	193	4.47	<10	0.86	762	<1	0.05	3	1670	18	<5	<20	53	0.08	<10	75	10	<1	70
33	80245	5	<0.2	1.72	15	105	10	1.57	<1	15	24	7	4.49	<10	1.12	945	1	0.06	2	1620	12	<5	<20	64	0.08	<10	70	10	<1	118
34	80246	5	<0.2	1.30	15	105	<5	2.24	<1	17	24	14	3.92	<10	0.87	801	<1	0.04	3	1880	10	<5	<20	50	0.07	<10	65	<10	<1	117
35	80247	5	<0.2	1.34	10	100	10	1.32	<1	15	32	16	4.03	<10	0.87	733	<1	0.06	1	1690	12	<5	<20	47	0.07	<10	87	10	<1	76
36	80248	5	<0.2	1.72	5	130	5	1.63	<1	14	24	24	4.70	<10	1.25	993	1	0.05	2	1610	10	<5	<20	46	0.07	<10	75	<10	<1	102
37	80249	5	<0.2	1.48	15	105	5	1.83	<1	15	28	16	4.85	<10	1.00	918	2	0.06	3	1850	12	<5	<20	47	0.07	<10	87	10	<1	94
38	80250	115	<0.2	1.00	20	85	10	2.68	<1	18	29	12	3.84	<10	0.62	799	<1	0.04	3	1590	18	<5	<20	44	0.08	<10	82	10	2	124
39	80251	235	<0.2	1.38	15	105	5	2.40	<1	19	22	37	4.04	<10	0.96	879	<1	0.06	2	1850	18	<5	<20	58	0.08	<10	75	<10	1	107
40	80252	20	<0.2	1.45	15	95	<5	3.04	<1	17	22	87	4.15	<10	1.04	913	<1	0.05	2	1890	14	<5	<20	87	0.08	<10	75	10	2	86
41	80253	5	<0.2	1.44	15	105	5	1.70	<1	11	19	29	4.25	<10	1.08	739	<1	0.05	2	1660	10	<5	<20	54	0.09	<10	82	<10	<1	51

42	80254	500	0.6	1.42	25	155	<5	2.06	<1	77	25	118	4.52	<10	1.10	698	1	0.04	2	1500	12	<5	<20	56	0.08	<10	75	10	<1	47
----	-------	-----	-----	------	----	-----	----	------	----	----	----	-----	------	-----	------	-----	---	------	---	------	----	----	-----	----	------	-----	----	----	----	----

QC/DATA:

Repeat:																														
1	60199	5	<0.2	1.58	15	80	<5	3.20	<1	9	32	30	3.16	<10	0.92	645	2	0.08	3	1690	12	<5	<20	81	0.02	<10	68	<10	1	56
36	60248	5	<0.2	1.81	15	135	10	1.83	<1	15	26	22	4.82	<10	1.28	968	1	0.05	3	1700	18	5	<20	48	0.08	<10	76	10	<1	110
Repeat:																														
1	60199	10	<0.2	1.59	15	85	<5	3.08	<1	9	36	35	3.09	<10	0.93	628	2	0.08	3	1570	10	<5	<20	83	0.02	<10	68	<10	1	58
10	60215	40	0.2	1.82	25	74	<5	5.01	<1	12	23	117	4.04	<10	1.13	1182	3	0.06	2	1410	20	5	<20	86	0.02	<10	83	20	<1	62
19	60224	30	0.6	4.24	36	55	<5	4.96	<1	36	8	151	9.63	<10	3.44	1726	12	0.04	5	1870	8	<5	<20	115	0.03	<10	285	40	2	90
36	60248	-	<0.2	1.76	15	130	<5	1.66	<1	15	25	24	4.80	<10	1.26	1001	1	0.05	3	1670	12	<5	<20	47	0.08	<10	75	<10	<1	107
Standard:																														
GEO97		125	1.0	1.84	85	155	<5	1.80	<1	20	80	79	4.31	<10	0.96	697	<1	0.01	24	710	20	<5	<20	61	0.12	<10	79	<10	5	77
GEO97		130	1.0	1.91	85	160	<5	1.80	<1	20	83	81	4.40	<10	0.96	701	<1	0.02	24	700	22	<5	<20	67	0.13	<10	82	<10	5	74

ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

df/1011d
 XLS/97Teuton
 Fax to Dina Vancouver 604-682-3992

24-Sep-87

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AK- 87-1043

TEUTON REBOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V8C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 14
Sample Type: Core
PROJECT #: None Given
SHIPMENT #: None Given
P.O.#: None Given
Samples submitted by: Not Indicated

Values in ppm unless otherwise reported

Et#	Tag#	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	60075	5	<0.2	1.20	20	120	<5	2.95	<1	9	31	148	2.71	<10	0.85	828	2	0.04	2	1510	10	5	<20	69	0.02	<10	48	<10	3	145
2	60078	5	0.2	1.20	30	120	<5	2.95	<1	9	31	144	2.79	<10	0.86	837	1	0.04	2	1540	12	<5	<20	64	0.02	<10	48	<10	3	147
3	60077	5	<0.2	1.44	5	130	<5	2.75	<1	15	28	48	3.34	<10	0.99	977	2	0.04	2	1520	10	<5	<20	53	0.04	<10	58	<10	2	307
4	60078	55	<0.2	1.55	25	75	<5	3.62	2	31	20	24	3.15	<10	1.14	1077	<1	0.03	<1	1530	18	<5	<20	65	0.04	<10	58	<10	3	333
5	60079	25	<0.2	1.52	25	130	<5	2.11	<1	9	27	68	3.29	<10	1.15	705	2	0.04	2	1570	10	5	<20	53	0.03	<10	68	<10	2	174
6	60080	5	<0.2	1.44	20	110	<5	2.44	<1	9	27	75	3.11	<10	1.09	721	2	0.04	<1	1550	10	<5	<20	65	0.02	<10	63	<10	<1	103
7	60081	5	<0.2	1.45	30	80	<5	1.92	<1	15	28	314	3.27	<10	1.09	712	1	0.04	2	1530	10	<5	<20	46	0.04	<10	70	<10	2	55
8	60082	5	<0.2	1.38	35	85	<5	2.78	<1	10	23	151	3.14	<10	1.03	728	2	0.04	2	1540	8	<5	<20	66	0.02	<10	67	<10	2	88
9	60083	250	0.2	1.38	50	70	<5	2.90	<1	13	28	232	3.57	<10	1.04	793	3	0.03	1	1490	12	<5	<20	75	0.02	<10	61	<10	1	79
10	60084	95	<0.2	1.60	15	85	<5	2.86	<1	10	18	191	3.41	<10	1.17	818	1	0.03	3	1490	14	<5	<20	72	0.05	<10	51	<10	2	81
11	60085	80	0.2	1.52	<5	255	<5	2.80	2	10	21	198	3.23	<10	1.02	794	1	0.03	1	1530	26	<5	<20	84	0.03	<10	46	<10	1	97
12	60086	40	0.2	1.38	10	195	<5	2.47	27	15	17	139	3.38	<10	0.86	876	1	0.03	1	1520	42	<5	<20	70	0.04	<10	46	<10	2	333
13	60087	115	0.4	0.97	15	85	<5	4.69	20	13	17	81	2.44	<10	0.50	834	2	0.02	<1	1510	22	<5	<20	80	0.01	<10	38	<10	3	413
14	60088	5	0.2	1.37	10	65	<5	1.52	2	12	14	81	3.31	<10	0.75	578	2	0.03	1	1570	18	<5	<20	38	0.02	<10	40	<10	1	172
QC/DATA:																														
Repeat:																														
1	60075	5	<0.2	1.13	30	105	<5	2.85	<1	9	28	137	2.87	<10	0.83	890	2	0.04	1	1500	12	<5	<20	64	0.02	<10	45	<10	3	144
Repeat:																														
1	60075	5	0.2	1.30	20	130	<5	3.15	<1	11	35	154	2.84	<10	0.86	960	2	0.05	2	1610	14	<5	<20	74	0.03	<10	54	<10	4	150
10	60084	-	<0.2	1.81	15	85	<5	2.85	<1	10	18	188	3.43	<10	1.16	817	1	0.03	2	1490	14	5	<20	72	0.05	<10	51	<10	2	81
Standard:																														
GEO97		165	1.4	1.74	65	155	<5	1.86	<1	18	66	81	3.95	<10	0.98	869	<1	0.03	23	650	22	<5	<20	81	0.12	<10	77	<10	5	66

dl/1011b
XLS/87Teuton
Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.
Frank J. Pazzotti, A.Sc.T.
B.C. Certified Assayer

22-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK- 97 1024

TEUTON RESOURCES CORPORATION
508-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 10
Sample Type: Rock
PROJECT #: Clone
SHIPMENT #: CL - 2
P.O.#: Not Given
Samples submitted by: Vic Velykovic

Values in ppm unless otherwise reported

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ce %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	V-97-1	180	19.4	0.85	285	95	<5	0.15	<1	12	74	238	7.61	<10	0.40	369	27	0.01	11	750	4690	<5	<20	7	<0.01	<10	36	<10	<1	462
2	V-97-2	80	14.8	0.35	150	45	<5	0.06	28	9	150	170	5.41	<10	0.08	111	15	<0.01	13	510	3856	<5	<20	2	<0.01	<10	15	<10	<1	1949
3	V-97-3	95	13.0	0.49	140	60	<5	0.09	4	10	166	187	4.43	<10	0.17	321	16	<0.01	11	550	1882	<5	<20	3	<0.01	<10	19	<10	<1	568
4	V-97-4	100	2.4	0.90	120	135	<5	0.13	<1	8	78	124	5.39	<10	0.44	171	15	<0.01	18	930	38	<5	<20	3	<0.01	<10	30	<10	<1	96
5	V-97-5	65	3.2	0.44	185	100	<5	0.10	<1	4	119	60	3.45	<10	0.13	70	18	<0.01	10	860	36	<5	<20	2	<0.01	<10	21	<10	<1	84
6	V-97-6	200	4.8	0.50	305	225	<5	0.11	<1	11	101	139	5.17	<10	0.11	187	15	<0.01	12	780	118	<5	<20	8	<0.01	<10	18	<10	<1	143
7	V-97-7	100	1.6	2.29	115	120	5	1.80	1	23	44	74	8.01	<10	1.81	1314	10	0.01	14	1180	18	<5	<20	37	<0.01	<10	67	<10	5	225
8	V-97-8	45	3.4	0.85	45	65	15	1.18	<1	59	63	12	7.93	<10	0.31	317	10	0.02	5	1210	48	<5	<20	28	<0.01	<10	28	<10	<1	18
9	V-97-9	115	0.8	2.09	35	100	30	1.14	1	80	77	13	>10	<10	1.28	733	18	0.04	5	280	18	<5	<20	13	<0.01	<10	57	<10	<1	51
10	V-97-10	75	0.8	3.18	105	80	30	3.03	<1	55	88	7	>10	<10	1.73	1550	17	0.01	5	320	8	<5	<20	43	<0.01	<10	68	<10	<1	38

QC/DATA:

Repeat:																															
R/S 1	V-97-1	205	19.8	0.91	275	105	<5	0.15	<1	13	85	227	7.78	<10	0.38	362	28	0.01	11	780	4888	<5	<20	5	<0.01	<10	38	<10	<1	475	
Repeat:																															
1	V-97-1	170	19.2	0.85	285	90	<5	0.18	<1	13	73	223	7.83	<10	0.39	370	26	0.01	12	770	4706	<5	<20	4	<0.01	<10	38	<10	<1	464	
Standard:																															
GEO'97		175	1.4	1.75	70	180	<5	1.73	<1	20	63	82	4.36	<10	0.92	688	<1	0.03	22	710	22	<5	<20	60	0.12	<10	79	<10	5	74	

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

dl/1008
XLS/B7Tauton
Fax to Dino Vancouver 604-682-3992

25-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 804-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK-97-1044

TEUTON RESOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 33
Sample Type: Rock
PROJECT #: None Given
SHIPMENT #: None Given
P.O. #: None Given
Samples submitted by: Not Indicated

Values in ppm unless otherwise reported

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	V 97-81	10	0.2	2.41	85	45	<5	0.83	<1	29	28	161	6.88	<10	1.81	1058	3	0.03	16	1930	10	<5	<20	18	0.07	<10	180	<10	4	39
2	V 97-82	>1000	12.2	2.70	>10000	60	<5	0.33	<1	183	32	3780	>10	<10	1.49	928	14	0.02	17	1120	30	<5	<20	6	0.02	<10	134	10	<1	38
3	V 97-83	80	0.6	2.87	935	50	<5	0.53	<1	34	32	170	7.38	<10	1.79	1128	5	0.02	15	1790	20	<5	<20	8	0.05	<10	160	10	7	43
4	V 97-84	70	0.4	0.75	290	95	<5	0.24	<1	20	73	24	4.08	<10	0.21	967	9	0.01	7	1140	8	<5	<20	2	<0.01	<10	17	10	5	8
5	V 97-85	970	2.0	1.12	450	40	<5	0.14	<1	35	102	132	8.30	<10	0.51	1178	15	0.01	12	820	14	<5	<20	1	<0.01	<10	27	10	<1	19
6	V 97-86	100	0.4	0.25	80	35	5	0.05	<1	16	87	15	4.23	<10	0.03	115	11	0.01	4	470	4	<5	<20	<1	<0.01	<10	9	10	<1	<1
7	V 97-87	90	1.0	0.50	110	40	<5	0.22	<1	23	83	118	4.76	<10	0.14	339	8	<0.01	15	1180	4	<5	<20	<1	<0.01	<10	20	10	<1	3
8	V 97-88	50	0.8	2.40	150	85	<5	0.41	<1	38	97	112	8.06	<10	1.42	2346	11	0.01	54	2170	18	<5	<20	4	<0.01	<10	107	10	4	37
9	V 97-89	125	6.8	1.36	295	50	<5	1.59	<1	15	60	278	7.88	<10	0.71	1285	13	0.01	41	800	22	<5	<20	7	<0.01	<10	53	10	<1	24
10	V 97-70	15	0.8	0.73	140	25	10	0.24	<1	13	47	6	5.58	<10	0.31	186	10	0.01	10	1270	18	<5	<20	<1	<0.01	10	17	10	<1	4
11	V 97-71	20	1.8	2.04	65	65	<5	2.12	<1	21	48	102	8.42	<10	0.96	2186	21	0.01	54	1580	28	<5	<20	22	<0.01	<10	84	10	<1	24
12	V 97-72	40	1.8	2.25	80	45	5	1.83	<1	21	81	90	6.14	<10	1.11	1941	21	0.01	51	940	28	<5	<20	17	<0.01	<10	77	10	<1	19
13	V 97-73	180	1.8	1.70	135	75	15	0.83	<1	41	69	46	9.00	<10	0.83	898	39	0.01	22	810	28	<5	<20	3	<0.01	<10	57	10	<1	23
14	V 97-74	15	1.2	2.60	55	105	<5	4.54	<1	18	29	82	6.58	<10	1.72	1779	13	0.01	29	1250	18	<5	<20	43	<0.01	<10	62	10	<1	15
15	V 97-75	55	3.0	2.33	135	55	5	3.54	<1	28	54	77	8.20	<10	1.60	3040	35	0.01	76	820	38	<5	<20	39	<0.01	<10	58	10	<1	18
16	V 97-76	15	1.0	1.82	60	50	<5	5.49	<1	10	41	79	4.10	<10	1.14	1962	5	0.01	12	430	8	<5	<20	60	<0.01	<10	17	<10	4	12
17	V 97-77	5	<0.2	1.47	10	1850	10	5.04	<1	8	32	3	4.23	<10	0.83	1258	3	0.01	2	1080	12	<5	<20	123	0.01	<10	31	10	2	132
18	V 97-78	15	1.6	2.51	70	65	<5	>10	7	25	25	125	7.19	<10	1.83	3388	7	0.01	5	810	70	<5	<20	221	<0.01	<10	60	<10	<1	434
19	V 97-79	5	0.8	2.53	50	95	10	1.80	<1	20	7	26	5.89	<10	1.85	1327	8	0.01	4	1070	22	<5	<20	20	<0.01	<10	35	10	2	85
20	V 97-80	5	<0.2	1.38	15	365	10	4.24	<1	11	21	7	3.97	<10	0.89	1109	3	0.01	4	830	12	<5	<20	79	0.02	<10	34	10	2	45
21	V 97-81	10	1.8	1.67	15	255	<5	1.89	<1	17	31	86	3.85	<10	0.95	1177	8	0.01	3	1040	22	<5	<20	28	<0.01	<10	22	10	<1	124
22	V 97-82	15	4.4	1.37	60	55	<5	1.25	8	17	38	32	5.23	<10	0.88	1382	14	0.01	5	900	134	<5	<20	21	<0.01	<10	20	<10	<1	419
23	V 97-83	75	8.0	2.91	45	70	<5	>10	<1	52	31	517	8.72	<10	1.69	8293	7	0.01	17	100	18	<5	<20	401	0.02	<10	115	10	<1	172
24	V 97-84	10	0.4	2.74	10	470	<5	5.67	1	15	11	28	4.95	<10	1.92	1753	3	0.01	6	1110	12	5	<20	125	<0.01	<10	30	<10	3	131
25	V 97-85	5	1.0	1.55	60	145	<5	>10	<1	13	21	70	3.71	<10	0.88	1759	10	0.01	13	1240	30	10	<20	218	<0.01	<10	39	10	6	52

ECO-TECH LABORATORIES LTD.

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1044

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	V 97-86	15	2.8	3.48	60	215	<5	1.02	<1	36	57	139	7.22	<10	2.98	1134	7	0.01	28	1590	40	5	<20	22	<0.01	<10	132	<10	<1	182
27	V 97-87	10	<0.2	5.92	35	100	10	7.88	<1	29	47	26	>10	<10	8.08	2050	7	0.02	18	1590	20	<5	<20	234	0.02	<10	283	10	<1	128
28	V 97-88	5	<0.2	3.99	15	105	<5	2.97	<1	42	12	94	8.10	<10	3.88	1814	7	0.03	9	1800	20	<5	<20	89	0.02	<10	247	10	<1	90
29	V 97-89	5	<0.2	4.35	<5	185	<5	1.85	<1	34	7	78	8.38	<10	4.32	1585	5	0.03	9	1980	18	<5	<20	54	0.02	<10	188	<10	<1	112
30	V 97-90	55	<0.2	4.12	20	105	<5	1.88	<1	34	27	124	8.35	<10	4.16	1101	6	0.02	13	1870	20	<5	<20	56	0.03	<10	181	10	<1	78
31	V 97-91	50	1.0	3.58	25	110	<5	1.88	<1	35	16	175	7.78	<10	3.35	1057	8	0.03	7	1770	28	10	<20	47	0.02	<10	173	10	<1	94
32	V 97-92	75	<0.2	4.25	30	70	<5	3.13	<1	39	27	175	9.18	<10	4.18	1129	5	0.03	13	2010	22	<5	<20	88	0.07	<10	238	10	<1	88
33	V 97-93	95	<0.2	4.74	55	75	<5	2.88	1	38	44	324	>10	<10	3.71	1518	9	0.02	15	1640	28	<5	<20	73	0.08	<10	220	10	<1	144

QC/DATA:

Repeat:																															
1	V 97-61	10	<0.2	2.58	50	60	<5	0.68	<1	31	28	156	7.01	<10	1.89	1072	4	0.05	18	2080	14	<5	<20	10	0.09	<10	190	20	5	45	
Repeat:																															
1	V 97-61	15	<0.2	2.42	70	40	<5	0.83	<1	29	26	160	8.74	<10	1.82	1073	4	0.03	12	1950	16	<5	<20	16	0.07	<10	181	10	5	41	
10	V 97-70	15	0.8	0.79	150	30	10	0.26	<1	14	50	7	5.84	<10	0.33	183	10	0.01	12	1340	20	<5	<20	<1	<0.01	<10	18	30	<1	8	

19	V 97-79	10	0.6	2.72	45	105	10	1.71	1	21	7	26	6.27	<10	1.78	1418	5	0.01	4	1180	22	<5	<20	20	<0.01	<10	38	30	2	83
Standard:																														
GEO'97		145	1.2	1.76	85	155	<5	1.73	<1	20	60	79	4.12	<10	0.95	690	<1	0.03	25	880	22	<5	<20	57	0.11	<10	78	20	4	71

df/1044
XLS/87Teuton
Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

25-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 8T4

Phone: 804-573-5700
Fax : 804-573-4957

ICP CERTIFICATE OF ANALYSIS - AK- 97-1045

TEUTON RESOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V8C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 8
Sample Type: ROCK
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
Samples submitted by: NOT INDICATED

Values in ppm unless otherwise reported

Et.#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
1	MM97-69	5	0.2	2.24	30	130	<5	2.85	1	35	177	151	5.18	<10	2.01	2275	3	0.02	68	1890	20	<5	<20	87	0.05	<10	204	<10	10	113	
2	MM97-70	5	<0.2	2.50	40	85	<5	6.23	<1	36	124	132	6.44	<10	2.37	2015	6	0.03	48	1710	18	<5	<20	194	0.03	<10	201	10	5	81	
3	MM97-71	5	<0.2	3.23	35	75	<5	5.94	<1	29	78	101	7.36	<10	2.54	2125	7	0.02	29	1770	18	<5	<20	189	0.01	<10	172	10	4	58	
4	MM97-72	35	0.8	3.00	45	90	<5	2.44	<1	38	83	145	7.84	<10	2.01	2138	15	0.01	43	2040	20	<5	<20	75	<0.01	<10	166	<10	5	83	
5	MM97-73	5	0.4	2.78	70	95	<5	0.67	<1	33	98	99	7.33	<10	1.85	2227	10	0.02	24	2200	28	<5	<20	30	<0.01	<10	158	10	10	131	
6	MM97-74	5	0.4	2.81	55	85	<5	1.19	<1	34	47	111	6.95	<10	1.79	1837	7	0.02	28	2170	22	<5	<20	40	<0.01	<10	158	10	7	74	
7	MM97-75	10	0.4	2.87	50	75	<5	3.56	<1	32	35	118	6.93	<10	2.02	2080	13	0.03	18	2210	22	<5	<20	128	0.01	<10	181	<10	7	116	
8	MM97-76	5	0.2	2.84	40	70	<5	2.53	<1	30	23	88	6.31	<10	1.84	1473	7	0.03	19	2300	20	<5	<20	83	<0.01	<10	178	<10	6	80	
QC/DATA:																															
<i>Repeat:</i>																															
1	MM97-69	5	0.2	2.07	30	110	<5	2.66	<1	33	156	141	4.88	<10	1.88	2114	3	0.02	62	1850	30	<5	<20	77	0.04	<10	190	10	10	102	
<i>Repeat:</i>																															
1	MM97-69	5	<0.2	2.18	30	125	<5	2.81	1	35	172	145	5.08	<10	1.96	2224	4	0.02	67	1910	22	5	<20	83	0.05	<10	200	<10	10	88	
<i>Standard:</i>																															
GEO'97		185	1.4	1.66	70	155	<5	1.86	<1	19	66	80	4.01	<10	0.95	709	<1	0.03	22	700	20	5	<20	96	0.09	<10	76	<10	6	72	

dl/1044
XLS/97Teuton
Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AK 97-1068

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

26-Sep-97

ATTENTION: DINO CREMONESE

No. of samples received: 37
Sample Type: Core
PROJECT #: Clone
SHIPMENT #: None given
Samples submitted by: Teuton

ET #.	Tag #	Au (g/t)	Au (oz/t)
14	60095	1.82	0.053
37	60156	4.14	0.121

XLS/97Teuton
Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

30-Sep-87

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK- 97-1068

TEUTON RESOURCES CORPORATION
508-875 W. HASTINGS STREET
VANCOUVER, B.C.
V5C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 37
Sample Type: Core
PROJECT #: Clone
SHIPMENT #: None Given
Samples submitted by: Teuton

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	80081	10	<0.2	1.82	<5	75	<5	2.40	<1	8	17	11	4.01	<10	1.41	785	1	0.03	2	1530	4	<5	<20	51	0.07	<10	45	<10	1	58
2	80082	10	<0.2	1.60	10	60	<5	2.49	<1	10	10	15	3.55	<10	1.17	729	<1	0.02	<1	1590	8	<5	<20	39	0.07	<10	41	10	3	105
3	80083	25	<0.2	1.43	15	90	<5	1.97	<1	10	18	14	3.33	<10	0.98	808	<1	0.03	<1	1660	8	5	<20	48	0.08	<10	41	<10	4	92
4	80084	5	<0.2	1.58	10	65	<5	1.81	<1	13	14	25	3.15	<10	1.19	708	1	0.03	<1	1820	8	5	<20	41	0.08	<10	48	<10	3	400
5	80085	5	<0.2	1.98	<5	95	<5	3.05	2	17	16	47	3.47	<10	1.54	997	<1	0.02	<1	1560	8	<5	<20	54	0.07	<10	49	<10	2	544
6	80086	5	<0.2	2.05	15	380	<5	1.89	<1	12	15	88	3.92	<10	1.47	887	<1	0.02	<1	1650	12	<5	<20	38	0.07	<10	47	<10	2	808
7	80087	10	<0.2	1.99	20	425	<5	3.13	2	36	18	24	4.20	<10	1.50	1124	<1	0.02	<1	1570	12	<5	<20	49	0.07	<10	52	<10	2	718
8	80088	5	<0.2	0.97	10	100	<5	2.02	6	8	15	61	2.53	<10	0.42	480	2	0.02	2	1870	12	<5	<20	48	0.02	<10	31	<10	3	538
9	80089	10	0.8	1.05	20	60	<5	0.73	1	10	17	82	2.73	<10	0.51	204	3	0.02	2	1770	10	<5	<20	19	<0.01	<10	28	10	2	107
10	80091	40	1.2	1.27	25	100	<5	1.45	<1	10	17	124	2.95	<10	0.78	496	3	0.02	<1	1480	24	5	<20	32	<0.01	<10	25	<10	2	80
11	80092	80	<0.2	1.83	20	315	<5	3.05	2	10	14	190	3.88	<10	1.11	737	4	0.02	<1	1640	40	5	<20	88	0.03	<10	50	<10	1	93
12	80093	145	0.4	1.54	20	95	<5	3.01	2	16	19	193	3.38	<10	1.00	850	3	0.03	<1	1570	24	5	<20	62	0.02	<10	39	10	2	96
13	80094	30	<0.2	1.39	20	230	<5	2.87	<1	24	18	69	3.11	<10	0.93	583	3	0.03	<1	1830	14	<5	<20	89	0.01	<10	43	<10	1	59
14	80095	>1000	0.4	1.50	115	100	<5	2.95	<1	97	15	241	3.39	<10	0.92	858	3	0.02	<1	1580	10	5	<20	85	0.02	<10	33	<10	2	90
15	80096	315	<0.2	1.83	55	285	<5	3.07	<1	41	22	103	3.38	<10	1.19	603	3	0.02	2	1540	10	<5	<20	89	<0.01	<10	28	<10	1	68
16	80097	75	<0.2	1.84	30	315	<5	4.34	<1	19	17	141	3.45	<10	1.28	708	3	0.02	<1	1550	6	5	<20	105	0.01	<10	37	<10	2	74
17	80098	30	<0.2	1.82	55	230	<5	4.36	<1	28	23	143	3.88	<10	1.13	732	4	0.02	1	1500	10	<5	<20	152	0.01	<10	40	<10	2	81
18	80098	158	<0.2	1.98	80	80	<5	4.12	<1	48	18	130	4.20	<10	1.38	774	3	0.02	<1	1520	4	<5	<20	109	0.01	<10	50	<10	<1	75
19	80131	5	<0.2	1.49	15	75	<5	1.10	<1	12	22	37	5.28	<10	1.03	1012	1	0.04	2	1820	14	<5	<20	33	0.08	<10	73	<10	<1	102
20	80132	10	<0.2	1.11	15	60	<5	1.70	<1	10	25	14	4.80	<10	0.86	756	2	0.04	1	1840	12	<5	<20	49	0.07	<10	75	<10	2	70
21	80133	10	0.4	1.42	10	100	<5	1.42	<1	20	40	116	4.10	<10	0.98	788	1	0.04	<1	1460	10	<5	<20	87	0.07	<10	61	<10	<1	101
22	80134	35	<0.2	1.58	15	80	5	1.47	<1	20	24	30	5.23	<10	1.22	824	2	0.03	<1	1540	14	<5	<20	40	0.08	<10	88	<10	<1	107
23	80135	65	<0.2	1.67	15	85	<5	2.87	1	23	28	34	5.01	<10	1.27	1104	2	0.02	1	1510	14	<5	<20	46	0.07	<10	82	<10	<1	248
24	80138	5	<0.2	1.38	15	95	10	1.11	<1	27	17	31	4.68	<10	0.94	827	2	0.03	3	1560	12	<5	<20	30	0.08	<10	69	<10	2	187
25	80137	5	<0.2	1.44	15	65	<5	2.22	2	17	24	6	5.08	<10	1.01	890	2	0.03	2	1580	8	<5	<20	44	0.08	<10	71	<10	2	115

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK- 97-1068

ECO-TECH LABORATORIES LTD.

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	80145	15	<0.2	1.27	15	470	<5	2.48	<1	8	18	88	4.28	<10	1.04	758	1	0.03	<1	1590	8	5	<20	75	0.08	<10	75	<10	2	43
27	80146	105	<0.2	1.57	15	150	<5	3.07	<1	71	17	16	4.14	<10	1.43	828	<1	0.03	<1	1810	6	<5	<20	59	0.07	<10	87	<10	2	42
28	80147	5	<0.2	1.91	15	60	10	1.88	<1	13	15	4	4.70	<10	1.68	828	<1	0.03	2	1820	8	<5	<20	39	0.08	<10	83	<10	<1	46
29	80148	5	<0.2	1.78	10	55	5	2.17	<1	12	17	7	4.48	<10	1.53	747	<1	0.03	2	1820	10	<5	<20	48	0.08	<10	88	<10	1	82
30	80148	385	<0.2	1.31	25	55	<5	3.03	<1	63	14	41	3.57	<10	0.99	590	<1	0.03	<1	1840	14	5	<20	77	0.07	<10	59	20	2	78
31	80150	5	<0.2	1.02	10	55	<5	3.57	<1	20	24	12	2.91	<10	0.83	548	<1	0.04	1	1660	8	<5	<20	83	0.07	<10	71	<10	3	48
32	80151	30	<0.2	1.28	15	55	5	2.70	<1	22	16	5	2.93	<10	1.15	578	<1	0.04	<1	1700	8	5	<20	73	0.08	<10	87	<10	3	52
33	80152	10	<0.2	1.38	15	40	<5	3.08	<1	25	23	15	3.20	<10	1.29	692	<1	0.05	2	1810	10	10	<20	82	0.08	<10	73	<10	2	81
34	80153	30	<0.2	1.28	15	55	<5	3.08	<1	35	17	43	2.89	<10	1.03	654	<1	0.05	1	1860	12	5	<20	78	0.08	<10	83	20	3	70
35	80154	140	<0.2	1.42	15	65	<5	2.88	<1	28	19	20	3.15	<10	1.12	704	<1	0.04	<1	1870	6	<5	<20	80	0.08	<10	54	<10	2	108
36	80155	180	<0.2	1.14	10	115	<5	2.48	1	27	14	96	3.15	<10	0.78	630	<1	0.03	1	1870	8	10	<20	49	0.07	<10	55	<10	3	184
37	80156	>1000	1.4	1.13	25	110	<5	2.12	<1	82	11	39	4.11	<10	0.74	659	2	0.03	<1	1850	14	<5	<20	48	0.08	<10	58	<10	2	185

QC/DATA:

Respt#:	Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	80081	10	<0.2	1.89	10	75	<5	2.51	<1	10	24	10	4.14	<10	1.44	808	<1	0.03	2	1660	8	5	<20	49	0.08	<10	47	<10	2	81	

36	60155	240	<0.2	1.14	10	115	<5	2.55	1	27	19	100	3.13	<10	0.76	636	<1	0.03	<1	1870	8	<5	<20	54	0.07	<10	58	<10	2	186	
Repeat:																															
1	80081	5	<0.2	1.77	<5	70	<5	2.35	<1	8	15	11	3.92	<10	1.37	788	<1	0.03	<1	1500	6	10	<20	48	0.07	<10	44	<10	<1	59	
10	80091	50	1.2	1.28	20	95	<5	1.48	<1	11	18	125	2.88	<10	0.77	489	3	0.02	2	1480	28	5	<20	33	<0.01	<10	25	10	2	79	
19	80131	5	<0.2	1.48	15	75	5	1.10	<1	12	22	36	5.27	<10	1.03	1018	2	0.04	1	1810	14	<5	<20	33	0.07	<10	73	<10	<1	102	
36	60155	190	<0.2	1.16	10	115	<5	2.53	1	28	15	99	3.21	<10	0.77	639	<1	0.03	2	1660	8	10	<20	51	0.07	<10	57	<10	3	166	
Standard:																															
GEO'97		120	1.2	1.90	50	185	<5	1.78	<1	20	59	60	4.46	<10	0.97	882	<1	0.03	25	860	20	<5	<20	68	0.13	<10	80	<10	4	71	
GEO'97		135	1.2	1.88	60	155	<5	1.79	<1	20	59	61	4.44	<10	0.96	669	<1	0.03	25	710	24	<5	<20	61	0.12	<10	78	<10	5	77	

dt/1068
XLS/97Teuton
Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AK 97 - 1071

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

1-Oct-97

ATTENTION: DINO CREMONESE

No. of samples received: 181

Sample Type: Core

PROJECT #: Clone

SHIPMENT #: CL - 16

P.O.#: Not Given

Samples submitted by: Dale Roberts

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	As (%)	Cd (%)	Co (%)
19	61947	1.20	0.035	-	-	-	-	-
27	61955	1.68	0.049	-	-	-	-	-
58	61986	40.10	1.169	-	-	4.16	-	0.346
59	61987	2.07	0.060	-	-	-	-	-
76	62004	16.52	0.482	-	-	1.54	-	0.148
77	62005	7.70	0.225	-	-	2.83	-	0.127
78	62006	1.34	0.039	-	-	-	-	0.020
79	62007	2.85	0.083	-	-	-	-	0.031
80	62008	18.35	0.535	-	-	2.90	-	0.282
123	62051	-	-	44.2	1.29	-	0.10	-
125	62053	1.20	0.035	-	-	-	-	-
126	62054	1.29	0.038	-	-	-	-	-

QC/DATA

Repeat:

58	61986	42.70	1.245	-	-	-	-	-
----	-------	-------	-------	---	---	---	---	---

Standard:

Su1a	-	-	-	-	-	-	-	0.041
------	---	---	---	---	---	---	---	-------

Mp-1a	-	-	-	-	-	-	-	-
-------	---	---	---	---	---	---	---	---

CD-1	-	-	-	-	-	0.70	-	-
------	---	---	---	---	---	------	---	---

XLS/97Teuton

Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

28-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AK- 97- 1071

TEUTON RESOURCES CORPORATION
908-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 181
Sample Type: Core
PROJECT #: Clone
SHIPMENT #: CL - 16
P.O.#: Not Given
Samples submitted by: Dale Roberts

Values in ppm unless otherwise reported

Et #	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	61929	5	<0.2	4.31	30	180	<5	4.85	<1	33	24	150	9.37	<10	4.23	1275	2	0.03	15	1780	<2	<5	<20	78	0.17	<10	250	<10	<1	57
2	61930	5	<0.2	4.27	30	200	5	6.42	<1	28	36	105	9.32	<10	4.26	1479	<1	0.03	18	1680	<2	<5	<20	101	0.17	<10	284	<10	<1	54
3	61931	5	<0.2	4.32	45	45	<5	5.02	<1	37	19	157	9.51	<10	3.92	1309	4	0.03	15	1810	2	<5	<20	73	0.12	<10	248	<10	<1	65
4	61932	5	<0.2	3.59	40	125	<5	4.42	<1	29	13	100	8.08	<10	3.44	1096	<1	0.03	5	2150	2	<5	<20	78	0.12	<10	200	<10	4	45
5	61933	5	<0.2	4.04	50	95	<5	3.22	<1	38	8	166	8.09	<10	4.27	1051	2	0.04	8	2180	2	<5	<20	68	0.13	<10	237	10	3	42
6	61934	5	<0.2	4.39	45	55	<5	4.56	<1	29	23	101	8.23	<10	4.72	1327	1	0.04	11	1920	<2	<5	<20	98	0.15	<10	255	10	3	47
7	61935	5	<0.2	4.60	40	285	10	6.23	<1	36	49	144	9.17	<10	5.10	1552	<1	0.03	24	1480	<2	<5	<20	179	0.17	<10	286	<10	<1	51
8	61936	45	2.4	3.68	55	110	<5	>10	2	20	31	4587	8.61	<10	3.50	1507	3	0.02	13	1140	<2	<5	<20	180	0.10	<10	232	30	10	109
9	61937	5	<0.2	3.88	40	75	<5	3.94	<1	28	5	181	9.09	<10	3.22	1362	5	0.04	11	1880	4	<5	<20	69	0.11	<10	266	<10	<1	92
10	61938	5	<0.2	3.20	45	60	<5	3.23	<1	27	10	235	7.38	<10	2.88	1078	6	0.04	8	1690	4	<5	<20	63	0.09	<10	155	<10	<1	80
11	61939	20	0.4	1.77	30	70	<5	4.05	<1	15	28	781	4.14	<10	1.32	704	5	0.04	<1	1450	2	10	<20	99	0.04	<10	70	<10	<1	90
12	61940	30	<0.2	1.88	40	75	<5	2.98	<1	18	14	287	4.41	<10	1.40	889	5	0.03	1	1500	4	<5	<20	65	0.05	<10	67	<10	<1	100
13	61941	25	0.2	1.53	30	65	<5	4.52	<1	12	25	609	3.46	<10	1.10	716	5	0.03	<1	1420	2	5	<20	104	0.04	<10	63	10	2	68
14	61942	35	0.4	1.88	50	85	<5	2.90	<1	23	15	597	4.57	<10	1.48	720	8	0.04	1	1510	8	5	<20	67	0.04	<10	67	<10	<1	113
15	61943	600	1.0	2.37	50	75	<5	4.30	<1	30	27	839	4.95	<10	1.75	972	3	0.02	<1	1430	8	<5	<20	89	0.04	<10	62	<10	<1	224
16	61944	560	3.2	2.81	295	60	<5	5.86	5	72	25	1901	>10	<10	2.13	1512	9	0.01	<1	1180	30	<5	<20	111	0.02	<10	87	<10	<1	587
17	61945	765	1.4	2.25	125	75	<5	4.04	3	85	22	688	4.83	<10	1.60	1140	4	0.03	<1	1510	8	<5	<20	91	0.03	<10	70	<10	1	444
18	61946	120	1.2	2.20	85	60	<5	3.74	2	29	14	1238	4.78	<10	1.46	1054	3	0.02	<1	1520	8	<5	<20	74	0.02	<10	55	<10	<1	330
19	61947	>1000	0.6	2.08	95	75	<5	3.00	<1	52	20	436	4.71	<10	1.31	831	5	0.02	1	1300	18	<5	<20	57	0.03	<10	63	<10	<1	385
20	61948	115	0.4	1.61	70	60	<5	4.67	<1	30	22	262	3.93	<10	1.10	853	3	0.03	1	1010	12	<5	<20	100	0.03	<10	70	<10	2	120
21	61949	10	<0.2	3.40	45	50	<5	7.11	<1	34	17	361	8.61	<10	2.84	1441	30	0.03	12	1470	12	<5	<20	186	0.07	<10	248	<10	2	74
22	61950	15	0.2	3.63	65	35	<5	7.38	1	45	16	482	9.94	<10	3.03	1520	53	0.03	17	1430	22	<5	<20	152	0.07	<10	281	<10	<1	72
23	61951	10	0.2	1.85	100	55	<5	4.08	<1	27	23	110	4.88	<10	1.34	940	8	0.03	2	1320	16	<5	<20	85	0.03	<10	88	<10	1	85
24	61952	35	0.4	2.19	80	90	<5	2.35	<1	26	25	121	5.83	<10	1.37	897	5	0.03	<1	1170	12	<5	<20	49	0.02	<10	75	<10	<1	140
25	61953	55	<0.2	2.08	240	50	<5	4.32	<1	35	32	64	5.39	<10	1.30	838	5	0.03	<1	1120	10	<5	<20	88	0.03	<10	76	<10	<1	119

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK- 97- 1071

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
26	61954	360	1.4	1.81	845	50	<5	4.93	<1	151	19	371	5.72	<10	1.19	948	4	0.02	<1	1050	22	<5	<20	84	0.02	<10	77	<10	<1	288
27	61955	>1000	1.0	2.18	125	60	<5	5.00	<1	28	19	531	5.88	<10	1.29	941	4	0.03	<1	1070	10	<5	<20	81	0.02	<10	113	<10	<1	235
28	61956	250	1.2	2.14	330	55	<5	5.38	<1	48	19	695	5.50	<10	1.27	1118	7	0.02	<1	1160	10	<5	<20	83	0.02	<10	76	<10	<1	185
29	61957	120	1.0	1.85	115	70	<5	4.43	<1	32	18	444	4.34	<10	1.16	984	5	0.03	<1	1500	12	<5	<20	105	0.02	<10	54	<10	<1	113
30	61958	950	2.2	2.05	540	55	<5	5.40	<1	33	19	480	4.58	<10	1.42	1121	11	0.02	<1	1260	14	<5	<20	102	0.01	<10	60	<10	<1	88
31	61959	260	1.2	1.85	135	55	<5	4.96	<1	20	21	303	3.85	<10	1.31	1041	8	0.02	<1	1310	18	10	<20	83	0.02	<10	57	<10	3	78
32	61960	130	0.6	1.95	445	45	<5	4.57	<1	35	15	203	3.95	<10	1.44	1060	7	0.02	<1	1360	12	10	<20	83	0.01	<10	51	<10	4	76
33	61981	10	0.2	1.82	845	55	<5	2.88	<1	41	15	94	3.83	<10	1.32	757	8	0.03	2	1590	10	<5	<20	50	0.02	<10	60	<10	2	50
34	61982	5	<0.2	1.82	60	55	<5	2.57	<1	12	15	72	3.87	<10	1.34	718	35	0.04	<1	1640	10	5	<20	46	0.02	<10	64	<10	2	49
35	61983	5	0.4	1.69	85	80	<5	1.89	<1	18	18	98	4.45	<10	1.33	846	8	0.03	<1	1630	12	<5	<20	31	0.02	<10	65	10	<1	55
36	61984	585	0.2	1.82	985	75	<5	3.91	<1	58	20	72	4.15	<10	1.40	922	9	0.02	<1	1450	4	<5	<20	65	0.02	<10	74	<10	<1	56
37	61965	60	0.4	1.77	2845	65	<5	5.78	<1	92	18	85	3.81	<10	1.20	1002	5	0.02	3	1490	14	10	<20	89	0.02	<10	64	10	2	49
38	61966	95	0.8	1.87	445	75	<5	4.32	<1	34	20	222	4.11	<10	1.38	851	4	0.02	<1	1800	10	5	<20	73	0.02	<10	61	<10	2	88
39	61967	10	0.4	1.74	70	60	<5	5.02	<1	21	21	148	3.85	10	1.16	901	3	0.03	2	1250	8	<5	<20	82	0.02	<10	79	<10	5	75
40	61988	10	0.4	1.89	30	55	<5	3.71	<1	17	23	87	3.79	<10	1.18	784	6	0.04	3	1520	10	5	<20	67	0.03	<10	69	<10	5	64
41	61989	55	<0.2	1.31	50	45	<5	4.65	<1	19	23	121	2.97	<10	0.85	888	4	0.04	3	1280	12	5	<20	87	0.05	<10	56	10	6	49

42	61970	5	<0.2	1.78	15	70	<5	3.37	<1	15	31	95	4.01	<10	1.19	666	3	0.08	3	1500	10	<5	<20	65	0.08	<10	78	<10	7	53
43	61971	5	<0.2	2.16	15	85	<5	2.20	<1	15	20	84	4.88	<10	1.54	709	2	0.05	2	1630	10	<5	<20	42	0.08	<10	75	20	5	55
44	61972	10	<0.2	1.88	15	70	<5	2.97	<1	14	33	63	4.15	<10	1.35	693	4	0.06	2	1700	10	<5	<20	53	0.08	<10	79	10	6	48
45	61973	10	<0.2	1.78	20	50	<5	2.82	<1	13	19	72	4.02	<10	1.28	842	7	0.05	2	1610	8	<5	<20	78	0.04	<10	86	30	4	48
46	61974	5	<0.2	1.71	25	60	<5	2.72	<1	13	24	71	3.99	<10	1.19	599	5	0.08	3	1690	8	5	<20	53	0.08	<10	72	<10	4	48
47	61975	10	<0.2	1.71	25	55	<5	3.32	<1	14	18	88	4.09	<10	1.18	675	10	0.05	2	1640	8	5	<20	79	0.07	<10	75	<10	5	80
48	61976	920	1.4	1.88	1255	70	<5	4.52	<1	136	26	334	6.89	<10	1.24	847	10	0.03	1	1490	22	<5	<20	77	0.04	<10	92	<10	<1	69
49	61977	75	0.2	1.74	285	80	<5	2.47	<1	49	23	178	4.21	<10	1.20	823	8	0.05	3	1820	8	5	<20	49	0.07	<10	80	<10	3	70
50	61978	60	<0.2	1.88	40	75	<5	2.51	<1	21	26	140	4.71	<10	1.24	694	7	0.06	2	1670	8	<5	<20	48	0.06	<10	88	10	3	71
51	61979	40	<0.2	1.88	235	70	<5	2.78	<1	48	18	118	4.78	<10	1.25	705	5	0.05	2	1710	12	<5	<20	58	0.07	<10	92	<10	3	69
52	61980	80	<0.2	1.81	945	70	<5	3.48	<1	88	21	86	3.86	<10	0.89	705	6	0.05	3	1700	10	<5	<20	88	0.08	<10	77	<10	3	72
53	61981	15	<0.2	1.58	40	60	<5	3.24	<1	17	19	89	3.83	<10	0.94	667	6	0.04	2	1710	8	5	<20	67	0.07	<10	61	<10	4	71
54	61982	35	<0.2	1.82	85	65	<5	3.10	<1	20	22	108	4.47	<10	1.27	699	7	0.04	3	1590	18	5	<20	59	0.05	<10	86	<10	2	71
55	61983	5	<0.2	1.84	50	60	<5	2.40	<1	15	11	48	4.27	<10	1.42	704	5	0.04	3	1760	12	10	<20	49	0.05	<10	75	<10	4	65
56	61984	90	<0.2	2.02	600	65	<5	4.81	<1	30	18	82	4.40	<10	1.41	1082	6	0.04	2	1810	14	10	<20	85	0.03	<10	68	<10	2	65
57	61985	258	<0.2	2.09	220	80	<5	5.00	<1	47	19	134	4.59	<10	1.38	1112	5	0.03	<1	1650	12	<5	<20	84	0.02	<10	87	20	2	68
58	61986	>1000	9.4	2.35	>10000	80	<5	5.81	<1	4281	3	831	>10	<10	1.37	1277	19	0.02	<1	1120	52	10	<20	138	0.01	<10	100	<10	<1	102
59	61987	>1000	1.0	1.69	895	85	<5	5.43	<1	116	16	121	4.24	<10	1.14	1051	4	0.03	2	1580	12	10	<20	121	0.01	<10	87	<10	2	60
60	61988	180	<0.2	1.89	145	50	<5	3.21	<1	34	18	97	4.51	<10	1.27	824	6	0.05	2	1730	12	10	<20	85	0.01	<10	85	20	<1	64

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK- 97- 1071

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
61	61989	305	<0.2	1.79	145	55	<5	4.09	<1	40	34	102	4.53	<10	1.17	842	9	0.06	3	1750	10	<5	<20	77	0.02	<10	96	<10	2	66
62	61990	95	0.2	1.42	45	40	<5	3.73	<1	21	19	102	3.87	<10	0.98	796	10	0.05	2	1720	12	<5	<20	72	0.02	<10	87	20	2	83
63	61991	125	<0.2	1.27	380	30	<5	5.38	<1	58	41	91	3.96	<10	0.78	901	11	0.07	3	1560	12	5	<20	100	0.02	<10	103	20	3	54
64	61992	80	0.4	1.59	275	40	<5	5.50	<1	54	33	104	4.83	<10	0.95	970	6	0.04	2	1060	16	<5	<20	125	0.02	<10	101	<10	2	64
65	61993	10	<0.2	4.82	58	60	5	7.07	<1	48	23	123	9.69	<10	4.79	1910	6	0.03	22	1770	26	5	<20	203	0.12	<10	334	30	2	124
66	61994	5	<0.2	4.89	75	65	<5	6.55	<1	58	18	131	>10	<10	5.17	1960	4	0.03	27	1830	24	<5	<20	174	0.21	<10	360	<10	2	239
67	61995	15	<0.2	4.38	60	50	5	8.89	<1	45	23	92	9.74	<10	4.25	2151	6	0.02	27	1750	22	<5	<20	203	0.20	<10	357	40	3	123
68	61996	275	<0.2	3.96	1825	50	<5	9.00	<1	219	27	182	9.72	<10	3.81	1849	5	0.03	20	1830	20	<5	<20	175	0.18	<10	315	30	2	90
69	61997	5	<0.2	4.52	85	70	10	8.25	<1	43	37	110	9.89	<10	4.42	1898	<1	0.04	29	1740	20	<5	<20	184	0.28	<10	324	30	4	88
70	61998	10	<0.2	4.41	50	55	15	7.88	<1	46	24	89	8.29	<10	4.48	1899	<1	0.04	21	2000	22	<5	<20	191	0.25	<10	316	<10	6	81
71	61999	10	<0.2	4.96	15	95	10	7.80	<1	43	43	84	8.91	<10	5.14	2040	<1	0.05	33	1700	8	<5	<20	179	0.27	<10	372	<10	3	94
72	62000	15	<0.2	3.83	45	60	<5	7.35	<1	41	40	122	8.47	<10	3.54	1880	7	0.04	24	1700	20	5	<20	198	0.21	<10	301	<10	4	85
73	62001	30	0.4	1.99	70	40	<5	3.57	<1	32	18	148	5.80	<10	1.48	943	10	0.05	6	1790	22	<5	<20	76	0.08	<10	147	20	2	71
74	62002	340	1.0	1.82	575	50	<5	7.13	<1	89	29	220	5.45	<10	1.31	1411	6	0.03	1	1110	18	<5	<20	119	0.08	<10	78	30	9	77
75	62003	420	0.8	1.94	260	60	<5	4.51	<1	79	33	224	5.91	<10	1.27	1171	5	0.02	<1	1180	24	<5	<20	75	0.09	<10	84	<10	4	79
76	62004	>1000	5.4	2.69	>10000	60	<5	6.12	<1	1399	12	522	9.85	<10	1.88	1966	24	0.01	<1	1790	42	<5	<20	139	0.02	50	96	40	2	155
77	62005	>1000	6.0	3.81	>10000	80	<5	3.56	<1	1213	19	1214	>10	<10	2.54	1848	41	0.02	<1	1230	88	<5	<20	54	0.02	<10	119	<10	<1	348
78	62006	>1000	1.0	2.92	1090	65	<5	3.54	<1	232	26	304	8.48	<10	1.87	1375	10	0.02	2	1440	34	<5	<20	59	0.02	<10	107	20	<1	139
79	62007	>1000	1.4	3.13	915	65	<5	3.04	<1	364	73	391	8.77	<10	1.88	1227	12	0.02	3	1130	34	<5	<20	48	0.04	<10	103	20	<1	118
80	62008	>1000	12.0	5.47	>10000	100	<5	4.03	<1	2736	<1	1945	>10	<10	2.82	2182	33	0.01	3	2050	98	<5	<20	75	0.02	<10	185	70	<1	285
81	62009	260	0.4	1.81	380	65	<5	3.88	<1	51	29	150	5.19	<10	1.14	1030	30	0.04	2	1710	32	<5	<20	58	0.03	<10	82	20	2	72
82	62010	640	0.4	1.91	95	55	<5	4.03	<1	19	23	98	4.30	<10	1.28	1085	10	0.03	3	1780	24	10	<20	57	0.05	<10	58	30	4	83
83	62011	10	0.4	1.81	35	50	<5	4.28	<1	16	27	94	3.97	<10	1.19	1037	15	0.03	1	1750	22	5	<20	69	0.04	<10	49	30	3	62
84	62012	160	0.2	1.84	205	45	<5	4.42	<1	28	15	89	4.27	<10	1.28	1229	15	0.03	<1	1740	28	10	<20	77	0.04	<10	56	10	2	98
85	62013	320	1.4	2.04	80	45	<5	4.52	13	18	17	191	5.37	<10	1.43	1350	28	0.04	3	1880	532	<5	<20	70	0.04	<10	79	<10	<1	978
86	62014	10	0.8	1.47	90	45	<5	3.61	4	13	31	117	3.78	<10	0.84	1083	12	0.04	2	1780	110	5	<20	69	0.02	<10	59	<10	2	381
87	62015	35	0.8	1.51	410	50	<5	3.87	<1	19	34	125	3.82	<10	1.01	981	20	0.04	2	1790	28	<5	<20	74	0.01	<10	71	20	3	81
88	62016	10	<0.2	2.35	205	50	<5	4.88	<1	38	35	158	6.25	<10	1.69	1098	8	0.03	5	2100	32	<5	<20	75	0.08	<10	144	40	3	83
89	62017	10	<0.2	4.01	120																									

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK- 97- 1071

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
96	82024	5	0.6	2.24	50	105	<5	5.93	<1	20	15	84	5.78	<10	1.84	1374	4	0.02	9	2130	32	<5	<20	131	0.01	<10	188	<10	<1	123
97	62025	90	1.2	2.47	90	80	<5	4.29	<1	28	20	81	7.53	<10	1.78	1149	8	0.02	8	2190	48	<5	<20	102	0.01	<10	214	<10	<1	119
98	82026	360	1.2	3.05	95	100	<5	4.06	<1	24	20	123	8.56	<10	2.35	1456	23	0.02	9	2250	40	<5	<20	97	0.02	<10	240	30	<1	124
99	62027	15	2.0	3.21	95	70	<5	3.05	<1	28	34	295	>10	<10	2.48	1149	9	0.01	16	2150	52	<5	<20	85	0.02	<10	264	20	<1	118
100	62028	10	1.2	3.09	90	90	<5	3.80	<1	22	23	217	>10	<10	2.35	1182	7	0.02	12	2250	44	<5	<20	86	0.02	<10	268	60	<1	108
101	62029	25	0.4	3.06	75	70	<5	3.70	<1	17	28	86	8.57	<10	2.48	1139	7	0.03	10	2330	36	<5	<20	101	0.02	<10	276	10	<1	98
102	62030	15	1.0	2.86	65	80	5	3.90	<1	19	28	108	8.79	<10	2.12	1159	7	0.04	10	2330	44	<5	<20	113	0.02	<10	262	40	<1	95
103	62031	140	2.2	3.12	170	65	<5	3.05	<1	29	30	172	>10	<10	2.39	992	17	0.03	15	2340	58	<5	<20	84	0.01	<10	246	40	<1	107
104	62032	15	2.0	1.67	105	65	<5	4.85	<1	34	27	188	8.04	<10	1.22	1058	6	0.02	18	2170	42	<5	<20	123	<0.01	<10	145	30	1	65
105	62033	45	3.4	2.46	115	80	<5	4.06	<1	47	22	299	8.80	<10	1.85	1033	8	0.03	10	2200	50	<5	<20	93	0.01	<10	227	30	<1	83
106	62034	15	1.2	3.05	40	85	<5	3.08	<1	26	18	108	9.00	<10	2.38	1067	8	0.03	7	2290	38	<5	<20	86	0.02	<10	293	<10	<1	87
107	62035	20	0.8	3.03	50	80	15	7.30	<1	28	23	39	8.12	<10	2.34	1557	7	0.03	4	2070	36	<5	<20	301	0.01	<10	232	<10	1	102
108	62036	30	1.0	3.88	85	105	10	3.44	<1	37	22	54	9.77	<10	3.27	1250	7	0.03	9	2430	48	<5	<20	91	0.01	<10	296	40	<1	127
109	62037	20	0.8	3.72	90	70	10	8.58	<1	31	27	47	9.05	<10	3.45	1788	8	0.03	10	2200	38	<5	<20	182	0.02	<10	304	<10	<1	130
110	62038	65	0.4	3.84	40	140	<5	6.32	<1	24	26	44	8.38	<10	3.31	2280	8	0.02	8	2040	40	<5	<20	234	0.01	<10	228	<10	<1	188
111	82039	75	0.8	3.91	35	105	10	5.64	2	29	30	41	9.95	<10	2.64	3250	7	0.01	8	1780	64	<5	<20	162	0.01	<10	151	<10	<1	396
112	62040	310	0.4	4.33	15	95	15	5.23	<1	53	8	48	>10	<10	2.89	3236	9	0.02	14	1740	48	<5	<20	127	0.01	<10	159	<10	<1	317
113	62041	35	0.2	3.62	15	130	15	4.90	<1	24	15	56	8.98	<10	2.35	2677	8	0.02	6	1770	42	<5	<20	94	0.01	<10	159	30	<1	250
114	62042	5	0.4	5.20	5	105	15	2.70	<1	25	10	83	>10	<10	2.71	4011	12	0.01	8	1810	48	<5	<20	47	0.01	<10	172	<10	<1	319
115	62043	5	<0.2	4.13	15	120	15	4.07	<1	24	42	20	9.59	<10	3.05	2159	8	0.02	9	1900	40	<5	<20	138	<0.01	<10	191	<10	<1	246
116	62044	10	<0.2	3.59	15	75	20	4.05	<1	20	53	19	8.87	<10	3.42	1409	4	0.04	8	2040	42	<5	<20	118	<0.01	<10	203	<10	<1	287
117	62045	10	<0.2	3.70	10	70	<5	4.41	<1	23	44	77	7.38	<10	3.71	1383	5	0.03	12	1820	34	5	<20	115	<0.01	<10	230	<10	<1	288
118	62046	5	<0.2	3.15	10	110	<5	5.42	<1	22	16	70	8.86	<10	2.54	1397	4	0.03	8	1790	38	<5	<20	175	<0.01	<10	137	<10	<1	214
119	62047	10	<0.2	3.27	10	275	10	3.83	<1	17	17	1	8.98	<10	2.47	1233	5	0.03	8	1830	28	<5	<20	78	<0.01	<10	123	<10	<1	204
120	62048	10	<0.2	3.11	15	170	<5	5.81	7	37	12	17	7.05	<10	2.15	1789	29	0.02	30	1810	38	145	<20	119	<0.01	<10	133	<10	<1	160
121	62049	5	<0.2	3.07	<5	370	5	5.91	5	13	18	<1	6.83	<10	2.33	1573	22	0.03	23	1800	28	110	<20	135	<0.01	<10	128	<10	<1	197
122	62050	5	<0.2	3.56	20	120	20	5.88	8	19	18	8	8.25	<10	2.76	1962	34	0.03	37	1790	38	170	<20	89	<0.01	<10	181	40	<1	188
123	62051	150	>30	4.83	180	90	<5	2.72	>1000	160	27	2494	>10	<10	2.31	4807	91	0.01	88	990	9430	310	<20	43	<0.01	<10	157	<10	<1	>10000
124	62052	5	<0.2	2.87	10	215	5	5.58	2	14	38	8	5.72	<10	2.24	1873	3	0.01	7	1820	42	10	<20	94	<0.01	<10	128	<10	<1	283
125	62053	>1000	1.0	2.86	55	120	<5	8.82	<1	22	24	73	7.71	<10	1.88	2464	14	0.01	5	1400	36	<5	<20	99	<0.01	<10	87	<10	3	232
126	62054	>1000	0.6	3.80	55	115	<5	5.15	<1	26	16	66	>10	<10	2.09	2802	10	0.01	3	1440	40	<5	<20	72	<0.01	<10	115	<10	<1	255
127	62055	25	0.2	3.05	40	75	10	3.56	<1	38	51	137	8.92	<10	2.35	1368	7	0.03	11	2000	44	<5	<20	58	<0.01	<10	175	<10	<1	218
128	62056	15	0.6	3.64	30	95	<5	6.81	<1	31	35	196	8.34	<10	3.00	1822	5	0.03	10	1980	40	<5	<20	134	<0.01	<10	186	10	<1	235
129	62057	10	<0.2	4.18	25	110	15	4.80	<1	32	37	31	9.41	<10	3.61	1552	8	0.02	8	1920	40	<5	<20	111	<0.01	<10	205	<10	<1	294
130	62058	15	<0.2	3.41	10	230	15	5.34	<1	28	46	15	7.59	<10	3.05	1411	5	0.02	8	2000	34	10	<20	121	<0.01	<10	199	20	<1	236

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK- 97- 1071

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
131	62059	10	<0.2	3.72	10	275	10	6.38	<1	23	38	3	8.40	<10	3.10	1918	6	0.02	11	1940	32	<5	<20	120	<0.01	<10	186	<10	<1	282
132	62060	90	1.0	4.29	55	105	<5	3.20	<1	46	31	203	>10	<10	2.71	3088	13	0.01	11	1800	50	<5	<20	57	0.01	<10	208	<10	<1	286
133	62061	75	1.6	3.82	95	100	<5	4.09	<1	45	28	210	>10	<10	2.64	2250	16	0.02	12	1830	62	<5	<20	67	0.01	<10	203	40	<1	319
134	62062	30	1.4	3.43	90	85	<5	5.47	<1	47	17	150	>10	<10	2.84	1782	8	0.03	11	1660	74	<5	<20	112	<0.01	<10	175	50	<1	255
135	62063	60	1.8	2.87	55	85	<5	5.77	<1	43	22	221	8.78	<10	2.13	1904	8	0.03	11	1720	64	<5	<20	121	<0.01	<10	175	<10	<1	196
136	62064	240	0.6	3.10	40	100	10	8.33	<1	22	29	83	7.43	<10	2.42	1854	13	0.02	7	1870	78	15	<20	118	<0.01	<10	150	20	<1	194
137	62065	120	0.2	3.18	15	205	5	4.26	<1	18	27	38	8.19	<10	2.14	2182	8	0.02	5	1830	68	<5	<20	82	<0.01	<10	159	<10	<1	205
138	62066	45	0.4	3.32	20	160	5	4.48	<1	28	26	89	9.08	<10	1.79	2158	10	0.01	10	1690	50	<5	<20	85	<0.01	<10	125	<10	<1	273
139	62067	75	<0.2	2.17	20	125	15	4.29	<1	19	24	3	5.78	<10	1.27	1728	7	0.02	5	1220	28	<5	<20	74	<0.01	<10	48	20	<1	142
140	62068	5	<0.2	2.91	20	165	10	5.28	<1	17	83	16	7.73	<10	1.83	1636	5	0.03	17	1550	42	<5	<20	148	<0					

144	62072	5	<0.2	4.56	10	95	10	4.40	4	20	261	33	>10	<10	3.57	1875	8	0.02	33	1690	8	<5	<20	148	0.02	<10	307	<10	<1	472
145	62073	5	0.2	3.74	10	95	10	3.45	1	22	211	107	9.53	<10	2.56	1782	6	0.02	44	1610	10	<5	<20	100	0.01	<10	230	<10	<1	212
146	62074	10	1.6	3.85	30	70	5	4.12	1	58	142	211	>10	<10	2.58	1712	24	0.02	48	1520	16	<5	<20	66	0.01	<10	193	<10	<1	250
147	62075	5	<0.2	3.99	10	150	20	1.73	<1	16	36	14	9.77	<10	2.51	1547	7	0.02	10	1490	10	<5	<20	33	<0.01	<10	196	<10	<1	218
148	62076	5	<0.2	3.72	<5	305	20	5.05	<1	14	36	8	8.86	<10	2.49	1965	5	0.02	7	1400	8	<5	<20	112	0.01	<10	202	<10	<1	167
149	62077	5	0.2	2.57	5	155	<5	3.18	<1	11	35	80	5.89	<10	1.58	1087	3	0.02	12	1350	6	<5	<20	88	<0.01	<10	114	<10	<1	126
150	62078	5	0.6	2.16	25	100	<5	4.15	<1	16	41	137	5.13	<10	1.44	1172	4	0.02	13	1650	10	<5	<20	119	<0.01	<10	175	<10	<1	78
151	62079	5	0.4	3.27	15	180	<5	4.53	<1	14	49	242	6.75	<10	2.38	1407	5	0.02	12	2300	4	<5	<20	112	0.01	<10	154	<10	<1	99
152	62080	5	0.8	3.72	15	185	<5	4.74	<1	17	52	402	7.59	<10	2.85	1384	5	0.02	14	2170	2	<5	<20	103	0.01	<10	159	<10	<1	108
153	62081	5	<0.2	3.48	10	180	<5	4.84	<1	14	53	161	7.27	<10	2.83	1284	8	0.03	13	2080	<2	<5	<20	119	0.02	<10	190	<10	<1	100
154	62082	10	0.8	3.50	50	75	<5	4.86	<1	21	30	127	7.82	<10	2.87	1641	5	0.02	12	1830	12	<5	<20	124	<0.01	<10	134	<10	<1	66
155	62083	15	1.6	3.83	45	110	<5	5.65	2	19	21	175	7.77	<10	2.57	1713	8	0.01	9	1690	14	<5	<20	170	<0.01	<10	116	<10	<1	182
156	62084	35	3.0	3.18	60	80	<5	6.76	<1	22	26	324	7.04	<10	2.80	1688	10	0.02	12	1680	14	10	<20	248	0.01	<10	148	<10	<1	108
157	62085	50	1.4	2.56	140	75	<5	6.44	<1	27	25	136	5.85	<10	2.00	1517	7	0.01	14	1670	14	<5	<20	217	<0.01	<10	91	<10	2	102
158	62086	65	1.0	2.98	70	95	<5	6.91	<1	21	25	113	6.53	<10	2.30	1597	7	0.02	18	1760	18	<5	<20	255	<0.01	<10	98	<10	<1	119
159	62087	135	0.8	3.70	70	80	5	4.44	<1	30	49	132	9.15	<10	2.67	1428	17	0.02	14	1460	28	<5	<20	147	<0.01	<10	154	<10	<1	200
160	62088	5	<0.2	3.19	10	85	<5	5.55	<1	14	22	32	6.83	<10	2.58	1427	5	0.03	8	1380	10	<5	<20	238	<0.01	<10	144	<10	<1	105
161	62089	5	<0.2	3.24	15	140	10	4.48	<1	16	58	27	7.15	<10	2.28	1249	3	0.02	14	1200	8	<5	<20	181	<0.01	<10	156	<10	<1	141
162	62090	5	<0.2	2.39	20	180	<5	4.52	<1	15	39	44	4.94	<10	1.50	1028	4	0.02	11	1120	12	<5	<20	189	<0.01	<10	89	<10	<1	98
163	62091	80	3.2	2.92	90	50	<5	5.18	1	44	95	486	>10	<10	1.87	1549	32	0.01	42	1210	56	<5	<20	130	<0.01	<10	111	<10	<1	183
164	62092	5	<0.2	3.53	25	130	<5	7.00	<1	17	31	57	7.47	<10	2.54	1701	11	0.02	7	1600	12	<5	<20	188	<0.01	<10	145	<10	2	142
165	62093	5	0.4	2.87	15	160	<5	3.43	<1	12	31	122	6.39	<10	1.86	1238	4	0.01	14	1970	12	<5	<20	88	<0.01	<10	138	10	<1	132

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK- 87- 1071

ECD-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
166	62084	110	2.6	3.75	70	60	<5	3.71	<1	51	66	359	>10	<10	2.11	1457	24	0.01	42	1770	28	<5	<20	80	<0.01	<10	171	<10	<1	154
167	62095	30	2.0	3.32	70	45	<5	3.10	<1	38	97	338	9.74	<10	2.12	1374	32	0.02	41	1360	22	<5	<20	72	<0.01	<10	158	<10	<1	123
168	62096	135	0.6	4.10	70	60	<5	3.10	<1	39	42	231	>10	<10	2.88	1586	13	0.02	4	1450	20	<5	<20	120	<0.01	<10	221	<10	<1	151
169	62097	30	<0.2	2.88	15	150	<5	4.05	<1	6	29	3	5.80	<10	2.34	1352	4	0.03	<1	1780	12	<5	<20	144	<0.01	<10	152	<10	<1	120
170	62098	5	<0.2	2.69	<5	770	10	4.84	<1	3	21	5	4.95	<10	2.33	1244	3	0.02	1	1710	10	15	<20	184	<0.01	<10	132	<10	<1	137
171	62099	10	<0.2	3.37	5	650	10	6.28	1	8	32	10	7.23	<10	2.31	1523	5	0.02	8	1830	26	<5	<20	183	<0.01	<10	134	<10	<1	181
172	62100	5	<0.2	2.84	30	115	5	5.87	1	15	24	27	8.73	<10	1.71	1459	7	0.02	7	1630	16	<5	<20	145	<0.01	<10	85	30	<1	168
173	62101	5	<0.2	3.71	10	220	15	4.98	<1	14	23	55	8.54	<10	2.57	1412	8	0.02	8	1650	16	<5	<20	168	<0.01	<10	147	<10	<1	231
174	62102	5	<0.2	3.15	10	350	10	5.71	<1	10	28	12	7.19	<10	1.83	1481	7	0.01	8	1750	26	<5	<20	169	<0.01	<10	96	20	<1	223
175	62103	5	<0.2	4.00	25	160	20	5.08	<1	15	16	2	6.83	<10	2.52	1577	7	0.01	8	1880	16	<5	<20	207	<0.01	<10	143	<10	<1	266
176	62104	5	0.6	3.99	10	180	<5	>10	8	15	18	77	9.88	<10	2.48	3323	9	0.01	7	1230	150	<5	<20	206	0.01	<10	131	<10	1	709
177	62105	25	2.0	3.24	20	70	<5	>10	8	17	27	183	9.12	<10	1.73	4914	24	0.01	8	920	300	<5	<20	311	0.01	<10	108	<10	8	638
178	62106	45	3.6	3.18	25	75	<5	>10	15	18	18	487	8.88	<10	1.78	5280	10	0.01	3	780	1234	<5	<20	283	0.02	<10	99	<10	11	958
179	62107	85	3.4	3.12	15	75	<5	>10	21	13	23	701	8.57	<10	1.80	6809	13	0.01	8	1190	522	<5	<20	445	0.02	<10	110	<10	11	1372
180	62108	30	1.4	3.72	5	130	<5	7.38	5	12	17	385	8.76	<10	2.37	2714	7	0.01	4	1100	30	<5	<20	192	<0.01	<10	80	<10	<1	500
181	62109	10	0.8	2.96	10	105	10	>10	10	15	25	90	7.11	<10	1.70	3632	7	0.01	10	1180	28	<5	<20	387	0.01	<10	71	<10	8	570

QC/DATA:

Repeat:																															
R/S 1	61929	5	<0.2	4.21	45	175	<5	4.91	<1	34	18	137	9.58	<10	4.14	1290	1	0.03	18	1840	<2	<5	<20	73	0.18	<10	249	<10	<1	84	
R/S 36	61964	530	<0.2	1.91	1010	70	5	3.93	<1	58	25	88	4.38	<10	1.38	941	9	0.02	1	1530	14	<5	<20	59	0.02	<10	75	<10	1	66	
R/S 71	61989	10	<0.2	4.90	30	75	15	7.89	<1	47	47	65	>10	<10	5.11	2146	<1	0.05	38	1880	10	<5	<20	173	0.27	<10	379	<10	3	108	
R/S 106	62034	15	1.2	3.13	45	75	<5	3.09	<1	28	20	110	9.42	<10	2.46	1112	9	0.03	8	2450	34	<5	<20	82	0.02	<10	299	30	<1	109	
R/S 141	62089	20	<0.2	3.36	25	100	10	4.29	3	29	231	60	8.43	<10	2.66	1494	6	0.03	47	1570	38	<5	<20	137	0.08	<10	288	<10	<1	232	
R/S 176	62104	5	0.6	4.08	10	140	10	>10	8	15	16	71	9.95	<10	2.53	3172	9	0.01	4	1330	116	<5	<20	202	0.01	<10	133	<10	1	630	
Repeat:																															
1	61929	5	<0.2	4.25	30	175	<5	4.80	<1	33	24	147	9.28	<10	4.19	1260	2	0.03	16	1780	<2	<5	<20	76	0.17	<10	248	<10	<1	69	
10	61938	5	<0.2	3.33	45	65	<5	3.37	<1	28	10	250	7.80	<10	2.78	1132	6	0.04	9	1800	8	<5	<20	84	0.10	<10	162	<1			

71	61899	10	<0.2	4.97	20	85	10	7.91	<1	48	46	87	>10	<10	5.18	2119	<1	0.05	34	1840	10	<5	<20	174	0.27	<10	377	70	5	105
80	62008	>1000	12.0	5.49	>10000	105	<5	4.28	<1	2764	<1	1958	>10	<10	2.81	2188	28	0.01	2	1970	82	<5	<20	82	0.02	<10	185	<10	<1	284
89	82017	10	<0.2	4.11	110	55	<5	6.05	<1	51	48	89	9.58	<10	3.63	1708	1	0.03	18	2280	34	<5	<20	111	0.18	<10	285	20	3	99
108	62034	15	12	3.07	55	80	<5	3.07	<1	28	18	107	9.03	<10	2.38	1081	8	0.03	5	2350	34	<5	<20	85	0.02	<10	294	<10	<1	99

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1071

ECO-TECH LABORATORIES LTD.

El #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
------	-------	---------	----	------	----	----	----	------	----	----	----	----	------	----	------	----	----	------	----	---	----	----	----	----	------	---	---	---	---	----

GC/DATA:

Repeat: Continued

115	62043	5	<0.2	4.07	15	110	15	4.01	<1	24	38	23	9.46	<10	3.02	2135	7	0.02	8	1850	44	<5	<20	137	<0.01	<10	188	<10	<1	320
124	82052	5	<0.2	2.85	15	215	10	5.82	2	14	38	5	5.78	<10	2.20	1880	4	0.01	7	1880	48	10	<20	90	<0.01	<10	128	<10	<1	285
141	62069	20	<0.2	3.25	20	100	<5	4.19	3	28	214	83	8.02	<10	2.78	1443	6	0.03	48	1520	32	<5	<20	131	0.05	<10	277	20	<1	220
150	82078	5	0.6	2.14	25	95	<5	4.17	<1	18	39	138	5.13	<10	1.43	1178	4	0.02	14	1690	12	<5	<20	118	<0.01	<10	173	10	<1	79
159	62087	140	0.6	3.65	65	80	<5	4.41	1	30	50	127	9.17	<10	2.82	1423	17	0.02	15	1460	28	<5	<20	147	<0.01	<10	152	<10	<1	205

Standard:

GEO'97	135	1.2	1.73	60	155	<5	1.78	<1	20	65	80	4.25	<10	0.95	698	<1	0.03	24	670	26	<5	<20	58	0.11	<10	77	<10	4	77
GEO'97	130	1.0	1.85	75	165	<5	1.91	<1	22	64	81	4.48	<10	0.97	723	<1	0.03	28	740	22	<5	<20	65	0.14	<10	85	<10	6	83
GEO'97	150	1.2	1.79	85	160	5	1.94	<1	23	66	77	4.81	<10	0.95	746	<1	0.03	28	770	22	<5	<20	61	0.14	<10	85	<10	6	80
GEO'97	135	1.2	1.79	80	170	<5	1.99	<1	23	69	75	4.74	<10	0.93	785	<1	0.03	31	820	24	<5	<20	61	0.14	<10	84	20	5	78
GEO'97	130	1.4	1.88	60	165	<5	1.84	<1	20	62	83	4.33	<10	1.01	721	<1	0.03	22	710	22	<5	<20	65	0.13	<10	84	<10	5	83
GEO'97	130	1.0	1.86	60	180	<5	1.92	<1	20	61	82	4.29	<10	1.00	745	<1	0.03	24	720	22	<5	<20	66	0.12	<10	81	<10	5	85

dl/1071/1071a/1071b
 XLS/97Teuton
 Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.
 Frank J. Pazzotti, A.Sc.T.
 B.C. Certified Assayer

CERTIFICATE OF ASSAY AK 97 - 1072

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

29-Sep-97

ATTENTION: DINO CREMONESE

No. of samples received: 98

Sample Type: Core

PROJECT #: Clone

SHIPMENT #: CL-15

P.O.#: None Given

Samples submitted by: Dale Roberts

ET #.	Tag #	Au (g/t)	Au (oz/t)
7	61837	1.08	0.031
23	61853	6.80	0.198
24	61854	24.40	0.712
25	61855	8.30	0.242
27	61857	0.82	0.024
33	61863	1.48	0.043
77	61907	5.90	0.172
78	61908	1.08	0.031
86	61916	3.45	0.101

XLS/97Teuton

Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

1-Oct-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK- 97-1072

TEUTON RESOURCES CORPORATION
508-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 98
Sample Type: Core
PROJECT #: Clone
SHIPMENT #: CL-15
P.O.#: None Given
Samples submitted by: Dale Roberts

Values in ppm unless otherwise reported

Et #.	Tap #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	61831	130	<0.2	1.67	15	115	<5	3.36	<1	15	38	89	4.85	<10	1.20	884	8	0.02	3	880	6	<5	<20	78	0.05	<10	41	<10	2	77
2	61832	240	<0.2	1.53	10	70	<5	3.10	<1	17	24	140	3.84	<10	1.08	715	2	0.02	3	970	6	<5	<20	69	0.03	<10	38	<10	2	77
3	61833	80	<0.2	1.58	5	230	<5	4.58	<1	13	28	135	3.80	<10	1.18	907	3	0.03	2	920	4	<5	<20	100	0.03	<10	41	<10	3	74
4	61834	230	<0.2	1.72	<5	60	<5	3.30	<1	14	22	94	3.83	<10	1.22	784	3	0.02	3	980	4	<5	<20	71	0.01	<10	32	<10	2	84
5	61835	65	<0.2	1.38	20	65	<5	3.81	<1	12	29	179	3.30	<10	0.96	827	3	0.03	2	950	4	<5	<20	83	<0.01	<10	49	<10	2	94
6	61836	75	0.2	1.56	10	65	<5	3.93	<1	16	22	258	3.10	<10	1.19	747	2	0.02	1	1200	6	<5	<20	88	0.01	<10	34	<10	3	85
7	61837	>1000	0.2	1.85	25	70	<5	4.42	<1	31	26	232	3.58	<10	1.47	721	3	0.03	1	1480	6	<5	<20	98	<0.01	<10	48	<10	<1	55
8	61838	75	<0.2	1.89	15	80	<5	3.94	<1	16	13	93	3.42	<10	1.55	715	3	0.03	<1	1570	4	5	<20	81	<0.01	<10	39	<10	3	97
9	61839	30	<0.2	1.82	20	80	<5	2.78	<1	14	13	40	3.33	<10	1.45	809	3	0.03	2	1570	4	<5	<20	55	<0.01	<10	36	<10	2	52
10	61840	60	<0.2	1.75	20	50	<5	3.53	<1	11	16	42	3.83	<10	1.41	717	3	0.04	<1	1560	6	5	<20	80	<0.01	<10	62	<10	1	34
11	61841	50	<0.2	1.78	30	55	<5	2.18	<1	17	21	53	3.70	<10	1.35	607	3	0.04	2	1550	6	<5	<20	44	<0.01	<10	54	<10	<1	31
12	61842	55	<0.2	1.85	40	55	<5	2.36	<1	21	15	74	3.60	<10	1.27	578	3	0.04	1	1540	8	<5	<20	38	<0.01	<10	52	<10	<1	29
13	61843	40	<0.2	1.53	35	65	<5	3.37	<1	18	15	81	3.20	<10	1.14	692	3	0.04	<1	1530	6	5	<20	86	<0.01	<10	52	<10	2	27
14	61844	25	<0.2	1.65	35	85	<5	1.57	<1	17	8	53	3.22	<10	1.21	450	2	0.03	1	1600	6	<5	<20	28	<0.01	<10	35	<10	<1	28
15	61845	40	<0.2	1.88	50	85	<5	1.52	<1	20	17	83	3.98	<10	1.42	524	3	0.04	2	1550	8	<5	<20	26	<0.01	<10	55	<10	<1	30
16	61846	45	<0.2	1.84	45	80	<5	1.37	<1	25	18	84	3.70	<10	1.28	441	4	0.04	3	1600	10	<5	<20	29	<0.01	<10	63	<10	<1	33
17	61847	75	0.4	1.68	125	75	<5	0.93	<1	140	13	152	4.09	<10	1.21	438	3	0.03	1	1590	12	<5	<20	32	<0.01	<10	46	<10	<1	60
18	61848	120	0.2	1.63	320	75	<5	1.35	<1	347	15	224	4.44	<10	1.09	437	4	0.02	<1	1610	12	<5	<20	30	<0.01	<10	37	<10	<1	74
19	61849	150	0.4	2.09	275	120	<5	0.49	<1	281	12	230	5.38	<10	1.47	478	4	0.01	<1	1580	10	<5	<20	11	<0.01	<10	41	<10	<1	134
20	61850	300	1.0	2.11	570	85	<5	0.75	<1	452	19	648	5.97	<10	1.41	665	6	0.01	<1	1460	8	<5	<20	13	<0.01	<10	51	<10	<1	167
21	61851	120	1.0	1.91	880	85	<5	0.70	<1	680	19	665	4.78	<10	1.23	514	4	0.01	<1	1570	10	<5	<20	11	<0.01	<10	36	<10	<1	185
22	61852	890	2.0	3.10	805	75	<5	0.45	<1	679	5	1500	8.05	<10	2.08	690	5	0.01	<1	1690	10	<5	<20	8	<0.01	<10	55	<10	<1	285
23	61853	>1000	13.2	2.44	>10000	65	<5	0.27	<1	1408	31	3058	>10	<10	1.41	504	28	0.01	<1	790	44	<5	<20	47	<0.01	20	67	<10	<1	204
24	61854	>1000	5.6	4.38	>10000	80	<5	0.41	<1	3511	3	1877	>10	<10	2.58	892	27	<0.01	<1	1410	34	<5	<20	20	0.01	10	187	<10	<1	212
25	61855	>1000	2.8	3.58	1780	60	<5	0.42	<1	624	12	728	>10	<10	2.38	771	12	0.01	<1	1500	14	<5	<20	19	<0.01	<10	95	<10	<1	188

ICP CERTIFICATE OF ANALYSIS - AK- 97-1072

ECO-TECH LABORATORIES LTD.

TEUTON RESOURCES CORPORATION

Et #.	Tap #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	61856	205	0.2	1.54	85	155	<5	0.95	<1	31	13	108	3.95	<10	0.98	482	4	0.02	2	1520	8	<5	<20	30	<0.01	<10	37	<10	3	83
27	61857	>1000	0.4	1.28	40	80	<5	1.09	<1	16	18	272	3.38	<10	0.80	377	2	0.02	1	1600	14	<5	<20	19	0.01	<10	37	20	2	58
28	61858	45	<0.2	2.24	60	210	10	1.78	<1	20	10	16	4.96	<10	1.38	749	<1	0.04	4	1980	14	<5	<20	232	0.19	<10	75	<10	5	97
29	61859	110	0.8	1.18	95	100	<5	0.94	<1	16	19	252	3.14	<10	0.87	373	3	0.01	2	1500	12	<5	<20	19	0.02	<10	36	<10	3	89
30	61860	190	0.6	1.03	75	115	<5	1.95	<1	24	9	174	4.81	<10	0.53	583	5	0.01	2	1420	14	<5	<20	41	0.02	<10	36	<10	4	58
31	61861	40	<0.2	1.04	15	110	<5	2.83	<1	12	18	117	3.32	<10	0.60	589	3	0.01	<1	1480	12	<5	<20	81	0.02	<10	29	<10	4	74
32	61862	60	0.4	1.14	10	105	<5	2.54	<1	12	9	283	3.08	<10	0.89	587	5	0.01	1	1550	12	<5	<20	59	0.01	<10	25	<10	3	89
33	61863	>1000	0.4	1.30	60	110	<5	2.48	<1	88	13	244	5.12	<10	0.89	698	5	0.01	<1	1400	8	<5	<20	54	0.03	<10	40	<10	2	90
34	61864	490	<0.2	1.28	45	105	<5	4.01	<1	59	11	93	4.88	<10	0.85	832	5	0.01	<1	1410	8	<5	<20	77	0.04	<10	34	<10	3	77
35	61865	70	<0.2	1.31	35	135	<5	2.17	<1	48	23	35	4.15	<10	0.86	587	3	0.03	3	1580	8	<5	<20	49	0.03	<10	40	<10	3	84
36	61866	120	1.2	2.80	95	55	<5	3.59	103	42	38	207	5.75	<10	2.39	1007	129	0.03	10	1710	594	<5	<20	128	0.02	<10	119	<10	<1	2044
37	61867	5	<0.2	4.07	10	80	<5	5.97	<1	32	31	193	8.03	<10	3.94	1484	5	0.03	11	1990	14	<5	<20	163	0.04	<10	231	<10	<1	137
38	61868	5	<0.2	3.53	15	85	<5	2.80	1	32	11	250	7.53	<10	3.41	1108	5	0.04	4	2230	24	<5	<20	78	0.03	<10	243	<10	1	83
39	61869	5	<0.2	3.57	20	60	<5	2.55	<1	31	12	203	7.42	<10	3.41	1114	5	0.04	5	2350	18	<5	<20	63	0.02	<10	220	<10	2	88
40	61870	575	<0.2	1.47	20	70	<5	2.20	<1	26	11	122	4.15	<10	1.07	639	3	0.02	2	1810	10	<5	<20	56	0.02	<10	45	<10	2	110
41	61871	35	4.2	1.36	10	75	<5	1.85	<1	9	8	2562	2.81	<10	0.98	528	2	0.02	<1	1600	24	<5	<20	38	<0.01	<10	25	<10	3	121

42	81872	5	0.8	1.95	5	100	<5	1.71	<1	9	5	494	3.01	<10	1.24	549	2	0.01	<1	1580	24	<5	<20	34	<0.01	<10	27	<10	3	154
43	81873	35	<0.2	1.38	10	95	<5	1.77	<1	7	14	22	2.47	<10	0.92	484	2	0.01	<1	1800	10	<5	<20	38	<0.01	<10	20	<10	4	134
44	81874	10	<0.2	1.57	10	75	<5	2.60	<1	11	7	7	2.95	<10	1.12	832	2	0.02	<1	1820	10	5	<20	58	0.01	<10	22	<10	4	119
45	81875	10	<0.2	1.54	5	125	<5	2.91	<1	12	8	11	3.05	<10	1.10	860	2	0.01	<1	1810	12	<5	<20	82	0.02	<10	25	<10	3	113
46	81878	40	1.2	2.33	15	70	<5	3.98	<1	28	21	781	4.94	<10	1.98	974	2	0.02	6	1670	14	5	<20	98	0.03	<10	71	<10	2	107
47	81877	5	0.6	3.71	15	80	<5	4.90	<1	30	28	330	7.02	<10	3.40	1334	4	0.03	8	2140	18	<5	<20	121	0.02	<10	155	<10	3	111
48	81878	5	<0.2	3.99	20	80	10	4.77	<1	28	57	38	7.89	<10	3.78	1471	5	0.03	12	2050	14	<5	<20	133	0.02	<10	201	<10	3	139
49	81879	5	<0.2	4.38	30	60	<5	5.18	<1	32	74	153	8.74	<10	4.21	1537	17	0.03	18	1870	28	<5	<20	120	0.02	<10	235	<10	<1	99
50	81880	30	0.4	4.09	25	105	<5	8.06	<1	38	66	202	8.22	<10	3.89	1730	12	0.03	21	1700	18	<5	<20	174	0.04	<10	257	<10	<1	114
51	81881	5	<0.2	3.81	10	835	<5	6.50	<1	30	59	137	8.34	<10	3.72	1471	4	0.03	15	1870	6	<5	<20	155	0.06	<10	241	<10	<1	87
52	81882	380	<0.2	3.81	90	485	<5	3.86	<1	131	70	407	9.14	<10	3.95	1382	6	0.02	16	1740	12	<5	<20	123	0.05	<10	254	<10	<1	122
53	81883	180	<0.2	3.88	5	770	<5	5.21	<1	29	58	154	7.87	<10	3.94	1410	4	0.03	15	1810	4	<5	<20	153	0.06	<10	246	<10	<1	63
54	81884	10	<0.2	3.75	10	745	<5	4.47	<1	30	48	151	7.85	<10	4.03	1298	3	0.04	14	2080	6	<5	<20	149	0.06	<10	242	<10	2	89
55	81885	105	0.4	4.23	30	80	<5	3.90	<1	53	52	178	9.03	<10	4.27	1278	3	0.03	13	2030	10	<5	<20	87	0.03	<10	248	<10	<1	92
56	81888	65	1.0	3.57	200	45	10	2.18	<1	40	35	121	>10	<10	3.45	1003	8	0.02	9	1970	28	<5	<20	80	0.03	<10	158	<10	<1	60
57	81887	35	<0.2	3.88	15	70	<5	3.88	<1	23	17	135	8.41	<10	3.88	1204	5	0.02	7	1780	6	<5	<20	80	0.04	<10	223	<10	1	47
58	81888	5	<0.2	3.81	10	145	<5	5.16	<1	29	61	91	8.86	<10	4.28	1429	4	0.02	14	1840	4	<5	<20	109	0.07	<10	251	<10	1	52
59	81889	5	<0.2	2.20	15	170	10	1.89	<1	14	12	11	4.25	<10	1.20	718	<1	0.04	5	1750	14	<5	<20	328	0.16	<10	68	<10	5	82
60	81890	5	<0.2	3.91	10	90	<5	4.56	<1	37	78	136	7.89	<10	4.48	1448	<1	0.03	15	2030	8	<5	<20	110	0.06	<10	258	<10	4	51

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1072

ECO-TECH LABORATORIES LTD.

Et.#	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	Li	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
61	81891	5	<0.2	3.76	35	50	<5	3.82	<1	36	51	135	7.55	<10	4.28	1328	4	0.02	13	2240	10	<5	<20	93	0.03	<10	212	<10	5	60
62	81892	5	<0.2	4.09	25	130	<5	4.73	<1	36	60	145	7.89	<10	4.55	1500	4	0.03	17	2000	8	<5	<20	119	0.04	<10	244	20	2	72
63	81893	10	<0.2	1.49	5	85	<5	2.02	<1	9	18	11	3.71	<10	1.15	863	2	0.03	2	1850	20	<5	<20	35	0.04	<10	55	<10	<1	188
64	81894	5	<0.2	1.38	5	70	<5	1.99	<1	10	38	12	3.55	<10	1.08	892	3	0.03	2	1590	18	<5	<20	39	0.03	<10	52	<10	<1	221
65	81895	65	<0.2	1.77	10	80	<5	1.97	<1	47	16	17	3.92	<10	1.46	901	3	0.03	2	1580	28	<5	<20	32	0.03	<10	71	<10	<1	190
66	81896	10	<0.2	1.57	10	65	<5	1.97	<1	22	23	89	3.18	<10	1.30	854	1	0.03	2	1810	18	<5	<20	39	0.03	<10	55	<10	<1	181
67	81897	25	0.4	1.55	10	80	<5	0.88	<1	12	12	205	3.21	<10	1.22	833	2	0.02	3	1570	28	5	<20	24	0.02	<10	48	<10	<1	216
68	81898	10	<0.2	1.48	10	55	<5	1.62	<1	18	20	38	3.43	<10	1.15	790	2	0.03	1	1830	18	<5	<20	29	0.03	<10	53	<10	<1	133
69	81899	15	<0.2	1.54	5	55	<5	2.01	<1	23	14	11	3.81	<10	1.25	789	2	0.03	<1	1570	18	<5	<20	31	0.03	<10	63	<10	<1	85
70	81900	60	<0.2	1.36	10	140	<5	2.77	<1	43	18	21	3.33	<10	1.12	742	1	0.02	<1	1590	20	<5	<20	40	0.04	<10	80	<10	1	81
71	81901	45	<0.2	1.08	10	55	<5	2.44	<1	18	18	12	3.03	<10	0.80	849	1	0.02	1	1620	20	5	<20	36	0.04	<10	43	<10	<1	83
72	81902	40	<0.2	1.37	10	55	<5	1.98	<1	20	17	33	3.25	<10	1.12	892	2	0.03	2	1810	10	<5	<20	32	0.03	<10	61	<10	<1	75
73	81903	55	<0.2	1.20	15	140	<5	2.07	<1	14	25	12	3.62	<10	0.89	817	2	0.03	2	1570	8	<5	<20	34	0.04	<10	85	<10	<1	54
74	81904	480	6.6	2.47	115	95	<5	1.90	4	55	25	4300	8.75	<10	1.85	1314	10	0.02	12	1730	38	<5	<20	41	0.08	<10	137	<10	<1	388
75	81905	210	<0.2	2.12	80	85	<5	0.69	<1	43	25	105	>10	<10	1.39	812	9	0.02	2	2200	14	<5	<20	18	0.06	<10	127	<10	<1	338
76	81906	295	<0.2	2.44	95	200	<5	0.65	2	91	24	751	9.91	<10	1.86	738	9	0.01	10	1860	12	<5	<20	17	0.06	<10	103	<10	<1	445
77	81907	>1000	<0.2	1.80	135	85	<5	0.79	1	113	20	219	>10	<10	1.11	438	19	0.01	18	2020	18	<5	<20	17	0.07	<10	118	<10	<1	291
78	81908	>1000	<0.2	3.58	105	60	<5	0.84	3	250	37	540	9.47	<10	3.08	1044	15	0.02	28	2100	8	<5	<20	18	0.07	<10	132	<10	<1	389
79	81909	95	<0.2	3.13	25	55	<5	0.89	<1	119	27	233	8.18	<10	2.84	915	5	0.01	17	2340	6	<5	<20	23	0.06	<10	138	<10	<1	137
80	81910	110	<0.2	2.95	20	70	<5	1.44	<1	74	52	224	7.83	<10	2.92	958	5	0.01	15	2110	6	<5	<20	29	0.05	<10	148	<10	<1	87
81	81911	30	0.6	2.38	30	50	<5	2.83	<1	45	29	693	8.68	<10	2.24	871	4	0.03	11	2340	4	5	<20	42	0.08	<10	131	<10	<1	58
82	81912	105	<0.2	2.83	45	35	<5	8.17	<1	43	37	527	7.07	<10	2.82	1340	3	0.03	14	2000	6	5	<20	73	0.08	<10	170	<10	<1	87
83	81913	385	<0.2	2.89	40	45	<5	5.91	<1	139	29	308	7.81	<10	2.74	1307	3	0.02	17	1770	6	<5	<20	52	0.09	<10	158	<10	<1	189
84	81914	35	0.8	2.87	35	80	<5	6.29	1	58	32	1043	7.88	<10	2.87	1423	6	0.02	18	1720	6	<5	<20	59	0.09	<10	180	<10	<1	140
85	81915	880	<0.2	3.38	35	55	5	4.64	<1	235	40	80	8.72	<10	3.58	1534	4	0.01	17	1690	4	<5	<20	50	0.09	<10	179	<10	<1	190
86	81916	>1000	<0.2	3.08	35	50	<5	3.22	<1	163	49	101	9.03	<10	3.34	1341	3	0.01	16	1800	<2	<5	<20	38	0.04	<10	178	<10	<1	184
87	81917	35	2.2	3.08	30	100	<5	5.39	<1	38	48	1778	6.43	<10	3.86	1478	4	0.03	14	1870	<2	<5	<20	63	0.04	<10	188	<10	<1	72
88	81918	10	<0.2	3.25	25	40	<5	5.84	<1	38	62	115	7.11	<10	3.88	1583	3	0.03	18	1840	<2	<5	<20							

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1072

ECO-TECH LABORATORIES LTD.

Et#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
96	61826	35	<0.2	3.07	45	40	<5	4.78	<1	36	44	71	8.93	<10	3.78	1375	4	0.03	14	1850	<2	<5	<20	68	0.04	<10	164	<10	<1	51	
97	61827	10	<0.2	3.12	25	50	<5	5.40	<1	30	29	103	7.16	<10	3.39	1180	<1	0.03	12	1880	4	<5	<20	76	0.11	<10	179	<10	<1	50	
98	61828	530	<0.2	3.42	100	80	<5	3.83	<1	90	13	139	8.87	<10	3.34	978	3	0.02	13	1880	8	<5	<20	56	0.06	<10	196	<10	<1	56	
QC/DATA:																															
Resplit:																															
1	61831	135	<0.2	1.58	15	70	<5	3.17	<1	15	39	87	4.36	<10	1.13	839	7	0.02	2	870	8	<5	<20	87	0.04	<10	38	20	3	74	
36	61866	80	1.2	2.71	100	50	<5	3.67	98	43	40	197	8.02	<10	2.48	1057	115	0.03	10	1750	596	<5	<20	129	0.02	<10	127	<10	<1	1731	
71	61901	55	<0.2	1.06	10	55	<5	2.36	<1	18	19	12	2.95	<10	0.77	624	1	0.03	1	1800	20	<5	<20	35	0.03	<10	42	<10	<1	80	
Repeat:																															
1	61831	120	<0.2	1.83	10	110	<5	3.30	<1	15	39	87	4.58	<10	1.17	870	8	0.02	1	890	8	<5	<20	73	0.04	<10	40	<10	2	81	
10	61840	80	<0.2	1.80	25	55	<5	3.53	<1	12	18	43	3.89	<10	1.44	725	2	0.05	1	1590	8	<5	<20	81	<0.01	<10	63	<10	2	34	
19	61849	120	0.4	2.07	275	120	<5	0.48	<1	277	12	229	5.35	<10	1.45	473	4	0.01	<1	1570	8	<5	<20	11	<0.01	<10	41	<10	<1	134	
36	61868	80	1.2	2.58	95	50	<5	3.55	101	42	37	204	5.89	<10	2.38	983	128	0.03	8	1710	588	<5	<20	127	0.02	<10	119	<10	<1	2028	
45	61875	10	<0.2	1.52	10	125	<5	2.83	<1	11	8	10	3.00	<10	1.08	845	2	0.01	<1	1800	12	<5	<20	69	0.02	<10	25	<10	3	105	
54	61884	10	<0.2	3.71	15	745	<5	4.47	<1	30	49	148	7.92	<10	3.98	1301	2	0.03	14	2070	8	<5	<20	147	0.06	<10	243	<10	2	70	
71	61901	45	<0.2	1.10	<5	55	<5	2.43	<1	19	16	14	3.06	<10	0.81	648	2	0.02	<1	1800	20	5	<20	37	0.04	<10	44	<10	1	81	
80	61910	120	0.4	2.80	15	75	<5	1.43	<1	71	51	213	7.93	<10	2.80	925	5	0.01	15	1880	2	<5	<20	33	0.02	<10	152	<10	<1	86	
89	61919	210	<0.2	3.14	15	40	<5	2.22	<1	40	23	127	8.61	<10	3.18	1289	4	0.03	10	2020	6	<5	<20	44	0.06	<10	185	<10	<1	71	
Standard:																															
GEO'97		140	1.2	1.54	85	150	<5	1.61	<1	20	50	78	3.78	<10	0.87	645	<1	0.02	24	640	20	<5	<20	50	0.09	<10	67	<10	3	65	
GEO'97		130	1.4	1.80	60	155	<5	1.85	<1	18	53	78	3.91	<10	0.90	663	<1	0.02	24	670	24	<5	<20	53	0.09	<10	70	<10	3	80	
GEO'97		130	1.2	1.56	50	150	<5	1.84	<1	18	51	78	3.87	<10	0.86	682	<1	0.02	24	680	22	<5	<20	53	0.08	<10	68	<10	3	87	

ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

df/1072
 XLS/97Teuton
 Fax to Dino Vancouver 604-682-3992

2-Oct-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 804-573-5700
Fax : 804-573-4557

ICP CERTIFICATE OF ANALYSIS - AK- 97- 1073

TEUTON RESOURCES CORPORATION
500-875 W. HASTINGS STREET
VANCOUVER, B.C.
V8C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 20
Sample Type: Rock
PROJECT #: Clone
SHIPMENT #: CL - 4
P.O.#: Not Given
Samples submitted by: Vic Veljkovic

Values in ppm unless otherwise reported

El #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	C14+50E 23+00N	25	<0.2	1.16	<5	50	<5	0.84	<1	11	52	203	2.12	<10	0.58	205	3	0.07	10	1460	10	<5	<20	38	0.08	<10	75	<10	1	18
2	C15+50E 23+25N	180	1.0	1.00	5	85	<5	0.57	<1	14	55	572	2.59	<10	0.71	272	<1	0.05	11	1950	8	<5	<20	32	0.09	<10	82	<10	<1	19
3	C14+50E 23+50N	155	1.6	2.38	<5	40	<5	0.87	<1	29	82	1361	5.03	<10	2.52	859	<1	0.03	29	1440	8	<5	<20	19	0.14	<10	188	<10	<1	43
4	C14+50E 24+75N	205	14.2	2.48	50	40	<5	1.23	5	19	72	817	6.15	<10	2.18	1214	2	0.03	17	1300	14	<5	<20	18	0.07	<10	218	<10	<1	478
5	C14+50E 27+25N	10	0.4	1.12	40	105	5	0.18	<1	30	12	41	4.58	<10	0.45	337	10	0.01	2	1040	10	<5	<20	2	<0.01	<10	33	<10	<1	15
6	C15+00E 23+25N	325	0.8	1.88	10	40	<5	0.58	<1	18	69	729	5.33	<10	1.49	351	98	0.04	13	1540	8	<5	<20	17	0.15	<10	178	<10	<1	60
7	C15+00E 23+50N	50	<0.2	1.49	<5	55	<5	0.62	<1	20	110	388	4.50	<10	1.55	315	<1	0.04	25	1380	4	<5	<20	21	0.13	<10	187	<10	<1	38
8	C15+00E 24+50N	10	0.4	2.28	15	80	<5	0.74	<1	25	69	278	5.41	<10	1.79	1401	5	0.01	15	1100	6	<5	<20	8	0.04	<10	81	<10	<1	55
9	C15+00E 25+25N	375	3.0	1.47	40	105	<5	0.43	<1	12	72	367	5.71	<10	1.00	417	11	0.02	7	1540	12	<5	<20	14	0.07	<10	115	<10	<1	42
10	C15+00E 25+75N	55	0.2	0.80	10	35	<5	0.68	<1	11	41	325	1.99	<10	0.79	419	3	0.03	9	1210	8	<5	<20	14	0.08	<10	68	<10	2	23
11	C15+50E 23+75N	60	1.0	3.85	<5	140	<5	1.70	<1	27	128	864	7.74	<10	3.28	1642	4	0.02	37	1690	8	<5	<20	28	0.06	<10	157	<10	<1	49
12	C15+50E 24+00N	520	4.2	1.62	15	50	<5	0.21	<1	85	85	1883	>10	<10	1.04	545	18	0.02	30	880	8	<5	<20	28	0.08	<10	88	<10	<1	35
13	C15+50E 24+50N	80	0.4	1.74	10	45	<5	0.72	<1	16	88	375	3.91	<10	1.78	418	<1	0.04	24	1610	4	<5	<20	27	0.10	<10	123	<10	<1	31
14	C15+50E 24+75N	20	0.2	1.27	10	70	<5	0.48	<1	26	57	173	3.88	<10	0.75	1104	4	0.01	11	1390	4	<5	<20	8	0.02	<10	36	<10	<1	16
15	C15+50E 25+00N	10	<0.2	2.00	<5	60	<5	1.94	<1	18	39	78	4.32	<10	1.82	866	3	0.03	10	1830	6	<5	<20	38	0.05	<10	122	<10	<1	43
16	C15+50E 26+25N	70	0.8	0.97	<5	55	<5	0.57	<1	12	55	278	3.05	<10	0.81	323	108	0.03	11	1810	8	<5	<20	22	0.09	<10	88	<10	2	48
17	C15+50E 26+50N	15	<0.2	3.43	10	95	<5	0.51	<1	32	218	441	7.51	<10	3.32	1230	15	0.02	39	1520	8	<5	<20	7	0.10	<10	262	<10	<1	59
18	C15+50E 26+75N	75	0.2	2.50	<5	40	<5	1.38	<1	15	117	688	4.82	<10	2.92	855	<1	0.03	34	1640	8	<5	<20	24	0.09	<10	140	<10	<1	42
19	C15+50E 27+00N	15	<0.2	2.09	20	50	<5	1.18	<1	28	93	454	5.04	<10	1.73	544	<1	0.05	30	2310	12	<5	<20	28	0.09	<10	141	20	<1	35
20	C15+50E 27+75N	10	<0.2	3.14	10	55	<5	7.11	<1	27	118	194	5.93	<10	2.83	1295	5	0.02	33	1400	2	<5	<20	209	<0.01	<10	152	<10	2	51

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK- 97- 1073

ECO-TECH LABORATORIES LTD.

El #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
QC/DATA:																															
<i>Repeat:</i>																															
R/S 1	C14+50E 23+00N	40	<0.2	1.08	10	40	<5	0.84	<1	11	40	207	2.09	<10	0.58	217	2	0.05	10	1480	8	<5	<20	31	0.07	<10	72	<10	<1	18	
<i>Repeat:</i>																															
1	C14+50E 23+00N	35	<0.2	1.20	<5	40	<5	0.97	<1	11	53	208	2.11	<10	0.58	207	3	0.07	10	1440	8	<5	<20	38	0.08	<10	77	<10	1	18	
10	C15+00E 25+75N	25	0.4	0.80	10	40	<5	0.67	<1	11	41	323	1.97	<10	0.79	419	3	0.03	9	1210	8	<5	<20	15	0.08	<10	68	<10	2	22	
<i>Standard:</i>																															
GEO'97		140	1.2	1.58	55	150	<5	1.65	<1	18	51	83	3.89	<10	0.89	851	<1	0.02	23	830	18	<5	<20	54	0.09	<10	70	<10	3	63	

CERTIFICATE OF ASSAY AK 97-1086

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

3-Oct-97

ATTENTION: DINO CREMONESE

No. of samples received: 90

Sample Type: CORE

PROJECT #: CLONE

SHIPMENT #: CL-18

P.O.#: NONE GIVEN

Samples submitted by: DALE ROBERTS

ET #.	Tag #	Au (g/t)	Au (oz/t)	As (%)	Co (%)
27	62227	1.24	0.036	-	-
39	62239	1.91	(0.056)	-	-
43	62243	8.30	0.242	3.37	0.237
60	62260	-	-	-	0.039
61	62261	-	-	-	0.023
71	62271	-	-	-	0.024
74	62274	2.25	0.066	-	-

Q/C DATA:

Repeat:

43	62243	8.48	0.247	-	-
----	-------	------	-------	---	---

Standard:

STD-M		1.65	0.048	-	-
CD-1		-	-	0.66	-

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

XLS/97Teuton

Fax to Dino Vancouver 604-682-3992

2-Oct-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK- 97-1088

TEUTON RESOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 90
Sample Type: CORE
PROJECT #: CLONE
SHIPMENT #: CL-18
P.O.#: NONE GIVEN
Samples submitted by: DALE ROBERTS

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	82201	25	0.6	2.05	125	105	<5	3.99	<1	28	32	105	4.88	<10	1.32	958	3	0.02	6	950	12	<5	<20	98	<0.01	<10	48	<10	<1	57
2	82202	50	0.4	1.97	45	85	<5	4.64	<1	18	33	109	4.54	<10	1.24	936	4	0.03	3	910	12	<5	<20	121	<0.01	<10	48	<10	<1	49
3	82203	25	0.4	2.03	40	85	<5	5.39	<1	18	32	82	4.42	<10	1.25	1040	5	0.04	3	880	10	<5	<20	115	<0.01	<10	48	<10	3	44
4	82204	5	0.4	2.17	55	75	<5	4.78	<1	19	35	84	4.87	<10	1.57	1048	5	0.04	3	850	10	<5	<20	107	<0.01	<10	63	<10	<1	46
5	82205	10	0.8	2.10	50	70	<5	4.28	<1	18	27	88	4.66	<10	1.54	945	4	0.03	3	870	12	<5	<20	91	<0.01	<10	70	<10	<1	52
6	82208	95	<0.2	1.97	20	75	<5	4.30	<1	14	38	6	4.09	<10	1.37	827	2	0.02	6	1390	4	<5	<20	98	<0.01	<10	91	<10	<1	53
7	82207	370	<0.2	1.88	105	85	<5	5.83	<1	16	30	9	4.15	<10	1.08	981	3	0.02	7	1330	8	<5	<20	134	<0.01	<10	61	<10	<1	60
8	82208	10	<0.2	1.94	80	60	5	4.87	<1	11	36	3	4.04	<10	1.53	937	2	0.04	8	1430	6	10	<20	111	<0.01	<10	98	<10	<1	54
9	82209	5	<0.2	2.09	20	85	<5	4.85	<1	12	37	3	4.12	<10	1.58	998	2	0.03	5	1400	6	<5	<20	101	<0.01	<10	115	<10	<1	85
10	82210	60	<0.2	2.05	25	85	5	4.15	<1	14	40	6	4.28	<10	1.80	890	2	0.03	7	1370	8	<5	<20	106	0.01	<10	130	<10	<1	59
11	82211	35	<0.2	1.94	70	70	<5	4.81	<1	9	42	4	4.55	<10	1.58	987	3	0.04	7	1340	8	5	<20	138	<0.01	<10	129	<10	<1	55
12	82212	100	<0.2	2.05	15	50	<5	5.32	<1	10	32	3	4.21	<10	1.61	1089	3	0.04	8	1380	4	<5	<20	105	<0.01	<10	130	<10	<1	75
13	82213	45	<0.2	1.86	<5	55	5	5.24	<1	8	34	2	3.62	<10	1.41	940	2	0.04	7	1370	<2	5	<20	94	0.01	<10	105	<10	<1	52
14	82214	490	<0.2	1.90	5	90	<5	5.80	<1	9	38	6	3.80	<10	1.50	985	2	0.04	7	1330	2	10	<20	102	<0.01	<10	123	<10	<1	52
15	82215	70	<0.2	2.08	40	180	<5	4.26	<1	14	41	60	4.15	<10	1.71	925	2	0.04	7	1380	12	5	<20	84	0.01	<10	138	<10	<1	57
16	82218	45	0.2	1.78	50	55	<5	4.73	<1	12	40	74	3.81	<10	1.50	988	3	0.04	7	1370	14	10	<20	81	0.01	<10	189	<10	<1	80
17	82217	980	0.8	1.97	1885	80	<5	4.53	<1	74	38	102	4.64	<10	1.32	935	12	0.04	2	1030	14	<5	<20	81	0.01	<10	98	<10	<1	64
18	82218	240	0.4	2.19	140	70	5	3.52	<1	14	18	109	5.73	<10	1.55	1085	5	0.04	2	920	12	<5	<20	84	0.01	<10	123	10	<1	88
19	82219	10	0.2	2.24	135	60	<5	2.98	<1	19	24	54	5.43	<10	1.80	1017	4	0.04	2	910	10	<5	<20	76	0.02	<10	96	<10	<1	46
20	82220	5	<0.2	2.31	90	80	<5	3.98	<1	17	25	41	5.53	<10	1.83	1128	3	0.04	3	890	12	<5	<20	87	0.02	<10	91	<10	<1	47
21	82221	410	0.4	1.96	840	55	<5	5.22	<1	75	40	83	4.39	<10	1.51	994	3	0.04	8	1370	18	5	<20	104	0.02	<10	106	40	1	54
22	82222	20	<0.2	2.25	90	50	<5	3.80	<1	23	36	27	4.43	<10	1.88	951	2	0.04	7	1480	8	<5	<20	95	0.02	<10	127	10	<1	82
23	82223	60	<0.2	2.02	135	55	<5	3.36	<1	21	47	40	3.98	<10	1.72	852	2	0.06	8	1460	16	<5	<20	102	0.02	<10	165	<10	<1	55
24	82224	30	<0.2	2.38	145	55	<5	3.72	<1	15	44	66	4.94	<10	1.95	931	3	0.04	9	1480	12	5	<20	109	0.01	<10	171	10	<1	58
25	82225	120	<0.2	2.39	750	45	<5	4.82	<1	32	38	89	5.26	<10	1.80	1020	3	0.04	8	1350	12	<5	<20	122	0.01	<10	160	<10	<1	57

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK- 97-1088

ECO-TECH LABORATORIES LTD.

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	82226	75	0.2	2.28	190	40	<5	7.08	<1	17	22	39	5.21	<10	1.81	1241	4	0.03	3	950	10	<5	<20	306	<0.01	<10	90	20	<1	54
27	82227	>1000	0.8	2.44	225	60	<5	3.86	<1	24	40	87	5.69	<10	1.93	922	8	0.04	8	1440	12	<5	<20	138	<0.01	<10	140	30	<1	61
28	82228	40	<0.2	1.84	190	35	<5	5.37	<1	21	32	48	4.08	<10	1.85	991	3	0.04	8	1390	12	10	<20	170	<0.01	<10	148	<10	<1	53
29	82229	20	<0.2	2.30	50	40	<5	5.13	<1	18	32	50	5.45	<10	1.90	1139	4	0.04	4	1010	12	<5	<20	113	0.02	<10	132	<10	<1	52
30	82230	25	0.2	2.03	110	70	<5	6.21	<1	16	21	39	5.21	<10	1.48	1342	4	0.04	3	850	12	10	<20	115	0.01	<10	86	<10	7	38
31	82231	10	<0.2	1.97	115	55	<5	5.19	<1	18	21	37	4.92	<10	1.61	1178	3	0.04	3	880	10	5	<20	89	0.06	<10	89	<10	3	39
32	82232	15	<0.2	2.33	115	90	5	5.83	<1	17	33	37	5.18	<10	1.78	1287	3	0.04	6	1230	14	5	<20	123	0.05	<10	119	<10	3	54
33	82233	20	<0.2	2.17	110	240	10	4.88	<1	19	41	24	4.58	<10	1.71	1052	1	0.04	6	1470	20	<5	<20	70	0.04	<10	135	80	3	57
34	82234	5	<0.2	2.28	20	150	5	4.52	<1	13	31	41	4.39	<10	1.93	949	1	0.03	7	1450	10	10	<20	73	0.05	<10	117	<10	<1	55
35	82235	35	<0.2	2.01	90	55	<5	4.23	<1	18	41	56	4.22	<10	1.71	863	3	0.04	7	1460	16	<5	<20	86	0.04	<10	148	10	<1	49
36	82236	75	<0.2	1.82	55	55	<5	4.92	<1	18	40	102	4.39	<10	1.51	962	3	0.04	6	1390	12	<5	<20	81	0.02	<10	172	<10	<1	54
37	82237	120	<0.2	1.90	30	80	<5	4.12	<1	18	114	77	4.56	<10	1.70	905	9	0.04	8	1420	14	<5	<20	78	0.01	<10	191	<10	<1	55
38	82238	65	<0.2	1.91	335	50	<5	4.91	<1	38	43	38	3.99	<10	1.84	921	3	0.05	10	1400	14	15	<20	85	0.01	<10	185	<10	<1	53
39	82239	>1000	1.0	2.18	545	60	<5	4.14	<1	66	40	190	4.84	<10	1.89	887	8	0.03	9	1450	24	10	<20	114	<0.01	<10	141	<10	<1	81
40	82240	800	<0.2	1.85	85	60	<5	4.55	<1	46	39	78	3.94	<10	1.36	812	2	0.04	6	1400	12	5	<20	89	<0.01	<10	137	<10	<1	56
41	82241	780	1.0	2.48	155	70	<5	8.31	<1	104	69	187	4.93	<10	1.83	1388	7	0.04	3	1500	18	<5	<20	145	0.01	<10	90	<10	4	75

42	62242	310	0.4	2.24	80	60	<5	2.43	<1	55	24	84	4.32	<10	1.81	761	4	0.03	2	1560	22	<5	<20	42	0.01	<10	70	<10	1	73
43	62243	>1000	6.2	2.49	>1000	45	<5	4.57	<1	1729	12	785	9.29	<10	1.87	1188	17	0.02	<1	1430	16	10	<20	73	0.01	<10	117	<10	<1	104
44	62244	70	0.4	1.87	270	40	<5	4.13	<1	31	38	117	4.83	<10	1.46	941	15	0.05	2	1360	10	<5	<20	58	0.03	<10	98	<10	2	48
45	62245	15	<0.2	1.82	80	55	<5	6.03	<1	14	21	79	4.27	<10	1.38	1212	8	0.04	<1	1420	10	5	<20	89	0.05	<10	90	<10	7	42
46	62246	45	0.4	2.03	50	40	<5	2.38	<1	25	33	151	5.01	<10	1.51	781	8	0.05	2	1420	10	<5	<20	43	0.04	<10	102	<10	<1	56
47	62247	10	0.2	1.92	25	30	<5	5.45	<1	13	19	76	4.58	<10	1.46	1130	10	0.03	2	1250	10	<5	<20	79	0.05	<10	85	<10	4	49
48	62248	25	0.2	2.05	35	40	<5	4.33	1	15	27	77	4.84	<10	1.83	1022	11	0.05	3	1520	12	5	<20	83	0.05	<10	91	<10	3	59
49	62249	20	<0.2	1.75	80	40	<5	2.76	<1	13	29	84	4.40	<10	1.42	784	9	0.05	2	1570	12	<5	<20	39	0.05	<10	81	<10	<1	54
50	62250	50	0.4	1.87	45	50	<5	3.88	<1	18	20	147	4.43	<10	1.37	845	21	0.04	2	1510	12	<5	<20	68	0.05	<10	84	<10	1	54
51	62251	25	0.2	1.87	30	50	<5	3.03	<1	14	23	142	4.38	<10	1.19	748	12	0.05	4	1570	10	<5	<20	49	0.05	<10	70	<10	1	46
52	62252	10	<0.2	1.77	20	50	<5	2.77	<1	15	25	182	4.62	<10	1.26	792	24	0.05	3	1620	12	<5	<20	51	0.06	<10	76	<10	<1	58
53	62253	240	1.0	1.82	135	50	<5	3.89	<1	41	16	361	4.19	<10	1.06	791	26	0.03	2	1520	18	<5	<20	81	0.04	<10	53	<10	1	78
54	62254	100	2.0	1.54	665	85	<6	3.79	<1	62	19	543	3.85	<10	0.89	748	23	0.02	2	1490	18	<5	<20	66	0.02	<10	40	<10	1	84
55	62255	455	1.8	1.72	880	65	<5	4.19	<1	46	15	485	4.29	<10	0.99	681	12	0.02	2	1590	12	<5	<20	68	0.02	<10	45	<10	1	71
56	62256	220	1.0	1.36	800	60	<5	3.02	<1	32	22	143	3.66	<10	0.78	657	19	0.03	2	1610	12	<5	<20	69	0.04	<10	38	10	2	51
57	62257	580	0.4	1.54	2250	50	<5	3.29	<1	94	39	125	3.77	<10	1.08	726	13	0.02	2	1570	14	5	<20	67	0.03	<10	52	<10	<1	57
58	62258	5	<0.2	1.51	40	110	<5	2.81	<1	31	24	40	3.62	<10	1.10	548	2	0.04	2	1600	12	<5	<20	81	0.03	<10	54	<10	<1	38
59	62259	5	<0.2	1.29	110	315	<5	1.84	<1	145	68	71	3.55	<10	0.97	426	5	0.04	3	1710	8	<5	<20	58	0.04	<10	60	<10	1	58
60	62260	555	<0.2	1.28	380	75	<5	2.14	<1	383	24	63	4.82	<10	0.77	388	3	0.02	2	1850	8	<5	<20	52	0.03	<10	52	<10	2	105

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1088

ECO-TECH LABORATORIES LTD.

Et.#	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
61	62261	40	<0.2	1.28	240	45	<5	1.42	<1	213	16	60	4.24	<10	0.83	343	3	0.01	<1	1460	8	5	<20	30	<0.01	<10	32	<10	2	95
62	62262	145	0.4	1.57	55	220	<5	1.52	<1	109	19	518	3.56	<10	1.15	374	3	0.02	2	1880	8	10	<20	47	0.01	<10	48	<10	<1	64
63	62263	30	<0.2	1.70	75	80	<5	1.94	<1	95	18	141	3.58	<10	1.38	429	3	0.02	1	1710	8	5	<20	52	<0.01	<10	41	<10	<1	51
64	62264	865	<0.2	1.53	30	280	<5	2.94	<1	23	21	95	3.95	<10	1.23	529	3	0.03	2	1640	8	5	<20	84	0.01	<10	54	<10	<1	42
65	62265	150	<0.2	1.34	15	265	<5	3.39	<1	9	19	82	3.45	<10	1.16	514	3	0.02	2	1580	6	10	<20	110	0.01	<10	53	<10	<1	35
66	62266	5	<0.2	1.49	<5	285	<5	2.88	<1	8	21	42	3.07	<10	1.30	504	2	0.04	<1	1680	8	5	<20	82	0.02	<10	54	<10	1	31
67	62267	5	<0.2	1.63	10	55	<5	2.89	<1	5	14	12	3.16	<10	1.51	547	2	0.04	1	1660	8	10	<20	77	0.01	<10	61	<10	2	35
68	62268	5	<0.2	1.44	15	55	<5	2.94	<1	9	19	39	3.18	<10	1.26	556	1	0.04	2	1590	6	5	<20	89	<0.01	<10	53	<10	<1	40
69	62269	5	<0.2	1.67	15	90	<5	1.90	<1	19	18	12	3.97	<10	1.54	819	2	0.03	2	1680	6	10	<20	51	0.02	<10	46	<10	<1	70
70	62270	30	<0.2	1.42	15	70	<5	1.06	<1	24	17	18	3.93	<10	1.27	558	3	0.02	2	1470	6	5	<20	33	0.02	<10	47	<10	<1	60
71	62271	485	<0.2	1.18	265	100	<5	2.33	<1	243	22	218	4.18	<10	0.82	480	3	0.01	<1	1540	8	<5	<20	92	0.02	<10	44	<10	<1	80
72	62272	45	0.6	1.28	135	75	<5	1.47	<1	189	13	843	3.24	<10	0.93	331	2	0.01	1	1790	8	<5	<20	44	0.02	<10	37	<10	<1	55
73	62273	775	0.4	1.83	50	80	<5	2.23	<1	69	17	587	4.93	<10	1.32	508	3	0.02	1	1630	8	<5	<20	87	0.02	<10	57	<10	1	56
74	62274	>1000	<0.2	1.79	70	75	5	1.87	1	37	13	35	6.96	<10	1.55	491	3	0.02	1	1520	8	<5	<20	60	0.02	<10	64	<10	<1	47
75	62275	220	<0.2	1.88	35	100	<5	1.18	<1	28	19	83	3.87	<10	1.75	441	2	0.02	1	1650	14	5	<20	41	0.02	<10	49	<10	<1	45
76	62276	20	<0.2	1.77	25	55	<5	3.60	<1	17	13	62	3.45	<10	1.58	723	2	0.03	2	1800	12	10	<20	125	<0.01	<10	51	<10	2	43
77	62277	75	<0.2	1.83	20	65	<5	2.39	<1	16	19	174	3.49	<10	1.37	541	3	0.03	1	1650	26	10	<20	68	<0.01	<10	52	<10	<1	57
78	62278	15	<0.2	1.64	15	80	<5	2.90	<1	10	13	54	3.26	<10	1.49	575	2	0.03	1	1700	8	10	<20	85	0.01	<10	53	<10	1	59
79	62279	5	0.2	1.47	15	50	<5	3.40	<1	9	18	91	3.19	<10	1.31	616	1	0.04	3	1840	8	10	<20	68	0.03	<10	56	<10	3	55
80	62280	15	<0.2	1.39	15	50	<5	4.44	<1	11	15	38	3.05	<10	1.22	744	1	0.03	<1	1570	8	5	<20	90	0.03	<10	59	10	3	44
81	62281	195	<0.2	1.49	30	65	<5	2.06	<1	23	18	105	3.83	<10	1.24	830	2	0.03	3	1680	8	5	<20	52	0.04	<10	48	<10	<1	73
82	62282	358	<0.2	1.40	45	65	<5	1.99	<1	37	27	16	4.02	<10	1.15	851	3	0.02	<1	1580	8	5	<20	80	0.05	<10	39	<10	<1	70
83	62283	25	0.4	1.08	20	70	<6	1.80	<1	15	26	321	3.02	<10	0.79	431	1	0.02	2	1580	8	10	<20	41	0.04	<10	45	<10	1	62
84	62284	160	5.0	3.41	85	60	<5	4.28	<1	36	20	288	>10	<10	2.48	1470	9	0.01	14	1970	40	<5	<20	85	0.01	<10	170	<10	<1	232
85	62285	185	2.0	3.71	55	80	<5	5.04	<1	33	18	147	8.78	<10	2.56	1648	7	0.01	8	1970	38	<5	<20	115	0.01	<10	186	<10	<1	229
86	62286	25	0.4	2.85	30	90	<5	3.41	3	18	11	44	7.83	<10	1.84	1129	4	0.03	1	1980	18	5	<20	112	0.01	<10	218	<10	<1	153
87	62287	80	1.0	3.15	80	75	<5	4.09	7	30	11	44	8.38	<10	2.15	1282	3	0.04	3	1990	24	<5	<20	127	<0.01	<10	254	<10	<1	143
88	62288	275	1.6	3.11	75	85	<5	4.42	8	31	13	71	8.20	<10	2.24	1308	6	0.02	2	1970	28	<5	<20	148	<0.01	<10	231	<10	<1	124
89	62289	50	1.0	2.67	85	75	<																							

TEUTON RESOURCES CORPORATION

IQR CERTIFICATE OF ANALYSIS - AK- 87-1088

ECO-TECH LABORATORIES LTD.

Et#	Tag #	Au(ppb)	Ag	As%	As	Ba	Bi	Ca%	Gd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
QC/DATA:																															
Resplit:																															
1	62201	45	0.6	2.08	125	115	<5	3.89	<1	28	48	101	4.88	<10	1.30	947	3	0.02	5	990	16	<5	<20	92	<0.01	<10	48	<10	<1	57	
36	62238	45	<0.2	1.82	80	95	<5	5.19	<1	18	42	97	4.44	<10	1.50	1027	4	0.04	8	1480	18	5	<20	82	0.02	<10	172	30	<1	57	
71	62271	520	<0.2	1.26	295	115	<5	2.46	<1	28	28	230	4.44	<10	0.65	507	2	0.01	<1	1590	10	<5	<20	98	0.01	<10	48	<10	1	83	
Repeat:																															
1	62201	30	0.4	2.07	145	105	<5	4.00	<1	27	33	104	4.68	<10	1.34	961	4	0.02	5	970	12	<5	<20	97	<0.01	<10	48	<10	<1	58	
10	62210	80	<0.2	2.10	30	95	5	4.13	<1	14	48	6	4.30	<10	1.62	962	3	0.03	7	1400	10	<5	<20	108	0.01	<10	132	<10	<1	59	
19	62219	10	<0.2	2.23	130	85	5	2.99	<1	8	24	54	5.45	<10	1.78	1021	4	0.04	3	900	12	5	<20	77	0.02	<10	96	<10	<1	48	
36	62238	70	<0.2	1.82	70	95	<5	4.86	<1	19	40	100	4.40	<10	1.52	998	3	0.04	7	1400	16	<5	<20	79	0.02	<10	172	<10	<1	55	
45	62245	15	0.2	1.89	75	80	<5	8.28	<1	14	22	81	4.40	<10	1.44	1258	8	0.04	2	1470	10	<5	<20	94	0.05	<10	93	<10	7	43	
54	62254	100	2.0	1.67	225	80	<5	3.98	<1	17	21	576	4.12	<10	0.96	790	22	0.03	2	1580	20	<5	<20	69	0.02	<10	44	<10	1	91	
71	62271	480	<0.2	1.24	270	105	<5	2.39	<1	247	23	220	4.30	<10	0.84	496	3	0.01	<1	1610	8	<5	<20	94	0.02	<10	45	<10	1	83	
80	62280	20	<0.2	1.44	10	55	<5	4.59	<1	11	18	38	3.18	<10	1.25	789	<1	0.04	2	1610	8	10	<20	93	0.04	<10	62	<10	4	47	
Standard:																															
GEO'87		140	1.2	1.75	55	153	<5	1.75	<1	19	59	81	4.05	<10	0.95	684	<1	0.03	25	670	20	<5	<20	59	0.11	<10	77	13	3	71	
GEO'87		130	1.2	1.71	80	155	<5	1.74	<1	19	59	79	4.06	<10	0.95	681	<1	0.03	25	680	26	<5	<20	58	0.11	<10	77	10	3	73	
GEO'87		135	1.0	1.72	70	170	<5	1.77	1	21	58	80	4.15	<10	0.96	686	<1	0.03	23	670	22	<5	<20	65	0.04	<10	78	<10	1	78	

dl:1088
 XLS/97Teuton
 Fax to Dinc Vancouver 604-612-3992

ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

CERTIFICATE OF ASSAY AK 97-1087

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

3-Oct-97

ATTENTION: DINO CREMONESE

No. of samples received: 91

Sample Type: CORE

PROJECT #: CLONE

SHIPMENT #: CL-17

P.O.#: NONE GIVEN

Samples submitted by: DALE ROBERTS

ET #.	Tag #	Au (g/t)	Au (oz/t)	Co (%)
26	62135	2.84	0.083	-
27	62136	2.07	0.060	-
31	62140	11.30	0.330	-
42	62151	1.00	0.029	-
44	62153	1.58	0.046	-
46	62155	0.62	0.018	-
66	62175	12.70	0.370	0.034
67	62176	8.40	0.245	-
80	62189	32.60	0.951	0.039

QC/DATA:

Repeat:

26	62135	2.75	0.080	-
----	-------	------	-------	---

Standard:

STD-M		1.45	0.042	-
-------	--	------	-------	---

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

XLS/97Teuton

Fax to Dino Vancouver 604-682-3992

2-Oct-87

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AK-97-1067

TEUTON RESOURCES CORPORATION
508-875 W. HASTINGS STREET
VANCOUVER, B.C.
V8C 1N2

Phone: 804-573-5700
Fax : 804-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 91
Sample Type: CORE
PROJECT #: CLONE
SHIPMENT #: CL-17
P.O.#: NONE GIVEN
Samples submitted by: DALE ROBERTS

Values in ppm unless otherwise reported

El.#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	82110	35	1.6	2.78	25	115	<5	7.05	<1	20	27	140	8.83	<10	1.62	2278	7	0.01	12	1480	24	<5	<20	221	<0.01	<10	73	<10	2	188
2	82111	80	1.8	2.78	20	105	<5	8.81	2	18	20	286	8.58	<10	1.85	2341	14	0.01	9	1410	14	<5	<20	253	<0.01	<10	78	<10	1	247
3	82112	550	2.6	3.95	20	70	<5	7.48	1	28	25	243	>10	<10	3.14	1860	144	0.02	14	1590	20	<5	<20	195	0.01	<10	200	<10	<1	142
4	82113	60	0.6	2.83	15	150	<5	8.71	<1	17	27	35	5.74	<10	2.07	1878	8	0.02	10	1830	14	<5	<20	206	<0.01	<10	91	<10	4	87
5	82114	15	1.0	2.81	10	150	<5	>10	2	13	39	108	8.53	<10	1.92	2688	11	0.01	8	1140	20	<5	<20	323	<0.01	<10	101	<10	4	148
6	82115	20	0.8	2.74	20	155	<5	>10	<1	11	26	86	5.39	<10	2.18	2224	8	0.02	10	1290	34	5	<20	387	<0.01	<10	76	<10	3	82
7	82116	5	1.0	1.54	20	95	<5	6.68	2	13	30	84	4.03	<10	0.77	1688	8	0.01	18	990	28	<5	<20	174	<0.01	<10	32	<10	3	266
8	82117	<5	1.2	1.52	50	70	<5	7.22	<1	17	38	66	4.28	<10	0.94	1538	10	0.02	29	950	12	<5	<20	218	<0.01	<10	38	<10	2	94
9	82118	<5	1.0	1.00	45	60	<5	6.58	<1	15	55	68	3.38	<10	0.87	1405	20	0.02	38	750	14	10	<20	201	<0.01	<10	27	<10	2	72
10	82119	<5	1.2	1.83	50	70	<5	3.97	<1	14	37	77	4.00	<10	0.81	914	8	0.02	34	820	12	<5	<20	99	<0.01	<10	28	<10	2	75
11	82120	<5	1.2	1.51	55	50	<5	5.17	<1	17	29	84	4.24	<10	0.87	1057	11	0.02	35	880	14	<5	<20	130	<0.01	<10	26	<10	2	60
12	82121	<5	1.4	1.64	30	85	<5	5.00	<1	14	44	58	4.00	<10	0.90	983	8	0.02	28	900	18	<5	<20	111	<0.01	<10	32	<10	2	82
13	82122	5	4.2	1.57	30	90	<5	7.88	1	15	42	58	4.20	<10	0.84	1200	8	0.04	22	890	24	<5	<20	228	<0.01	<10	31	<10	2	98
14	82123	5	2.6	1.99	45	65	<5	4.04	4	22	42	202	5.04	<10	1.21	1145	19	0.02	33	1140	176	<5	<20	95	<0.01	<10	70	<10	<1	680
15	82124	5	1.8	1.14	55	55	<5	4.66	<1	16	63	61	3.95	<10	0.83	1141	17	0.02	38	910	44	<5	<20	128	<0.01	<10	25	<10	1	158
16	82125	10	1.2	1.63	40	65	<5	4.12	<1	14	37	83	4.21	<10	0.90	1123	8	0.02	30	790	14	<5	<20	108	<0.01	<10	29	<10	2	86
17	82126	5	1.2	1.80	40	65	<5	3.83	<1	15	31	69	4.53	<10	0.99	1013	9	0.02	33	880	20	<5	<20	123	<0.01	<10	33	<10	<1	99
18	82127	5	1.6	1.39	35	60	<5	4.86	<1	13	47	80	3.80	<10	0.71	1454	12	0.02	35	720	22	<5	<20	123	<0.01	<10	30	<10	2	132
19	82128	5	1.8	0.88	85	50	<5	4.75	<1	13	85	87	3.24	<10	0.44	1146	25	0.02	53	540	18	<5	<20	156	<0.01	<10	45	<10	2	33
20	82129	15	1.8	0.74	75	40	<5	1.42	<1	15	83	80	2.99	<10	0.34	488	26	0.02	60	570	20	<5	<20	31	<0.01	<10	68	<10	2	43
21	82130	25	0.8	1.88	80	70	<5	5.21	<1	17	28	94	4.92	<10	1.33	1099	8	0.03	7	900	22	<5	<20	128	<0.01	<10	54	<10	<1	57
22	82131	210	1.0	2.23	130	70	<5	3.12	<1	23	25	94	5.80	<10	1.59	838	8	0.03	4	930	22	<5	<20	83	<0.01	<10	65	<10	<1	55
23	82132	130	0.8	2.01	110	80	<5	3.01	<1	17	40	72	4.84	<10	1.43	838	5	0.03	8	1290	20	<5	<20	76	<0.01	<10	92	<10	<1	56
24	82133	90	1.2	2.16	435	75	<5	4.43	<1	39	31	103	5.47	<10	1.41	1038	5	0.03	6	1120	24	<5	<20	93	<0.01	<10	87	<10	<1	65
25	82134	140	1.0	1.83	140	85	<5	4.09	<1	18	25	79	4.81	<10	1.26	1159	4	0.03	5	1230	18	<5	<20	87	<0.01	<10	76	<10	2	56

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1067

ECO-TECH LABORATORIES LTD.

El.#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	82135	>1000	1.8	2.26	855	75	<5	4.72	<1	34	38	149	8.16	<10	1.42	1071	20	0.03	8	1540	22	<5	<20	122	<0.01	<10	79	<10	<1	84
27	82136	>1000	1.8	2.43	2770	60	<5	4.27	<1	208	21	103	8.18	<10	1.63	959	9	0.02	6	1050	32	<5	<20	80	<0.01	<10	60	<10	<1	69
28	82137	180	1.4	2.30	305	70	<5	4.59	<1	30	26	107	5.85	<10	1.47	973	6	0.03	4	820	30	<5	<20	148	<0.01	<10	50	<10	<1	62
29	82138	305	0.8	2.05	190	60	<5	4.93	<1	24	26	54	4.73	<10	1.31	932	4	0.02	3	1010	18	<5	<20	122	<0.01	<10	55	<10	<1	64
30	82139	20	<0.2	1.95	25	70	<5	6.33	<1	8	35	5	3.94	<10	1.37	1052	3	0.04	5	1380	8	<5	<20	107	<0.01	<10	94	<10	<1	64
31	82140	>1000	4.2	2.89	425	65	<5	5.11	<1	81	29	200	7.55	<10	1.87	1207	13	0.02	20	1520	26	<5	<20	97	<0.01	<10	107	<10	<1	77
32	82141	485	0.8	2.18	150	65	<5	5.58	<1	24	35	44	4.80	<10	1.61	1208	4	0.03	7	1470	18	<5	<20	88	0.01	<10	88	<10	1	58
33	82142	375	1.0	2.04	340	75	<5	7.51	<1	30	21	73	4.80	<10	1.38	1227	8	0.03	4	980	18	5	<20	108	<0.01	<10	87	<10	2	63
34	82143	5	0.4	2.18	75	60	<5	5.38	<1	16	33	53	4.80	<10	1.62	1074	4	0.04	5	1240	18	<5	<20	104	<0.01	<10	113	<10	<1	58
35	82144	5	0.2	2.23	40	60	<5	4.98	<1	12	37	32	4.77	<10	1.78	1009	3	0.04	6	1440	12	10	<20	88	0.02	<10	133	<10	<1	58
36	82145	285	0.8	2.18	230	85	<5	3.38	<1	33	36	55	4.90	<10	1.65	823	3	0.04	7	1470	14	<5	<20	61	0.01	<10	137	<10	<1	53
37	82146	30	0.4	2.07	125	60	<5	4.15	<1	22	40	42	4.42	<10	1.67	821	2	0.04	8	1420	18	<5	<20	82	0.02	<10	118	<10	<1	56
38	82147	<5	<0.2	2.41	30	85	<5	3.78	<1	15	39	31	4.99	<10	1.97	919	2	0.03	5	1480	14	<5	<20	68	0.03	<10	111	<10	<1	67
39	82148	<5	<0.2	2.45	50	60	<5	3.21	<1	19	43	25	4.98	<10	2.17	887	3	0.04	8	1510	22	10	<20	84	0.03	<10	142	<10	<1	72
40	82149	25	0.8	2.28	30	50	5	3.98	<1	15	39	77	4.99	<10	1.98	815	3	0.04	7	1480	20	<5	<20	73	0.02	<10	186	<10	<1	72
41	82150	5	0.4	2.13	35	85	<5	4.37	<1	13	40	79	4.73	<10	1.87	842	2	0.04	7	1420	16	<5	<20	100	0.03	<10	167	<10	<1	72

42	82151	>1000	0.8	2.48	870	55	<5	5.57	<1	44	37	99	8.25	<10	1.84	1049	5	0.03	6	1380	24	<5	<20	109	0.02	<10	164	<10	<1	75
43	82152	10	<0.2	1.76	90	40	<5	5.25	<1	13	40	28	3.63	<10	1.54	784	2	0.05	6	1460	30	<5	<20	93	0.02	<10	174	<10	<1	57
44	82153	>1000	0.4	2.13	110	50	<5	4.45	<1	18	52	44	4.33	<10	1.89	828	3	0.05	7	1520	30	5	<20	84	0.03	<10	189	<10	<1	62
45	82154	725	0.4	2.84	1500	50	<5	4.23	<1	115	27	152	6.71	<10	2.39	1027	6	0.04	8	1830	22	<5	<20	111	0.04	<10	218	<10	<1	104
46	82155	>1000	0.8	2.83	90	45	<5	5.20	4	21	29	201	7.00	<10	2.31	1324	11	0.03	8	1230	14	<5	<20	120	0.05	<10	210	<10	<1	308
47	82156	35	0.2	3.35	100	45	<5	5.97	<1	34	23	155	8.67	<10	2.91	1550	13	0.04	13	1770	18	<5	<20	85	0.05	<10	234	<10	2	108
48	82157	40	0.6	1.81	85	35	<5	3.91	1	15	20	101	4.78	<10	1.36	847	7	0.05	2	1580	18	<5	<20	72	0.01	<10	101	<10	<1	60
49	82158	5	0.4	1.84	85	80	<5	3.75	<1	20	38	88	4.55	<10	1.29	850	8	0.05	2	1580	14	<5	<20	89	0.01	<10	75	<10	<1	48
50	82159	5	0.2	2.14	50	60	<5	3.36	<1	17	20	67	4.84	<10	1.80	921	8	0.03	1	1640	14	<5	<20	56	0.02	<10	69	<10	<1	47
51	82160	10	0.4	2.03	60	65	<5	3.11	<1	16	42	76	4.82	<10	1.42	787	9	0.05	3	1510	12	<5	<20	87	0.01	<10	71	<10	1	54
52	82161	15	0.6	1.73	55	50	<5	3.44	<1	12	36	185	4.56	<10	1.21	787	11	0.05	3	1610	14	<5	<20	96	<0.01	<10	84	<10	1	52
53	82162	15	0.8	1.83	10	50	<5	3.18	<1	16	38	126	4.51	<10	1.31	843	10	0.04	3	1200	18	<5	<20	84	0.02	<10	55	<10	3	85
54	82163	10	0.8	1.95	35	45	<5	4.10	2	20	45	108	4.45	<10	1.40	1013	5	0.03	3	1030	24	<5	<20	62	0.04	<10	58	<10	4	240
55	82164	180	1.4	1.70	60	65	<5	4.43	<1	17	45	272	4.08	<10	1.04	840	6	0.04	3	1360	24	<5	<20	78	0.02	<10	54	<10	4	180
56	82165	300	2.2	1.45	185	65	<5	7.51	<1	43	24	545	3.98	<10	0.82	1277	4	0.02	<1	1510	18	<5	<20	120	<0.01	<10	45	<10	4	123
57	82166	140	1.0	1.71	105	70	<5	3.68	<1	58	22	273	4.50	<10	1.01	825	6	0.02	2	1580	18	<5	<20	67	<0.01	<10	45	<10	2	120
58	82167	45	0.6	2.00	80	80	<5	2.15	<1	38	21	105	4.79	<10	1.34	678	18	0.03	3	1680	16	<5	<20	41	<0.01	<10	48	<10	<1	58
59	82168	15	0.4	1.96	15	55	<5	4.02	<1	11	27	68	4.19	<10	1.33	825	10	0.04	<1	1580	14	<5	<20	82	<0.01	<10	45	<10	2	41
60	82169	15	0.4	2.18	20	85	<5	1.78	<1	13	53	72	5.08	<10	1.53	810	4	0.04	3	1700	16	<5	<20	50	0.01	<10	59	<10	<1	44

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1087

ECO-TECH LABORATORIES LTD.

Et#	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
61	82170	25	0.8	2.08	130	65	<5	5.90	<1	19	22	105	5.85	<10	1.19	1136	5	0.04	3	1500	18	<5	<20	105	0.03	<10	55	<10	<1	37
62	82171	15	0.2	1.83	45	85	5	3.84	<1	17	24	19	4.35	<10	1.23	729	3	0.04	<1	1670	18	<5	<20	80	0.03	<10	54	<10	2	30
63	82172	10	0.2	1.81	30	50	5	3.78	<1	16	24	18	4.29	<10	1.28	702	3	0.05	2	1750	12	<5	<20	78	0.04	<10	58	<10	3	33
64	82173	5	0.2	1.59	45	50	<5	3.11	<1	21	24	25	3.79	<10	1.08	605	3	0.06	4	1730	14	<5	<20	68	0.01	<10	53	<10	2	36
65	82174	5	0.4	1.47	80	70	10	2.21	<1	40	24	27	3.53	<10	0.97	482	3	0.05	3	1740	12	<5	<20	50	0.01	<10	40	<10	<1	47
66	82175	>1000	5.4	0.74	470	50	<5	0.31	<1	331	34	2064	>10	<10	0.31	138	18	0.01	1	1080	30	<5	<20	11	0.02	30	42	<10	<1	53
67	82176	>1000	1.0	1.83	175	315	5	1.71	<1	110	12	27	6.98	<10	1.45	532	5	0.03	<1	1630	12	<5	<20	86	0.02	<10	60	<10	<1	67
68	82177	50	0.4	2.07	25	380	<5	1.95	<1	17	17	138	4.67	<10	1.78	604	3	0.02	<1	1640	12	<5	<20	86	<0.01	<10	48	<10	<1	40
69	82178	85	0.2	1.58	55	80	<5	2.94	<1	10	23	85	3.38	<10	1.35	601	5	0.04	2	1700	18	10	<20	74	<0.01	<10	44	<10	<1	38
70	82179	25	0.4	1.31	65	45	<5	1.87	<1	19	18	104	4.44	<10	1.00	567	3	0.03	2	1730	20	<5	<20	44	0.02	<10	36	<10	<1	57
71	82180	310	0.4	1.66	40	85	<5	1.81	<1	15	24	69	4.57	<10	1.25	629	4	0.02	2	1720	18	<5	<20	53	0.01	<10	43	<10	<1	63
72	82181	60	<0.2	1.34	15	460	<5	2.71	<1	13	19	102	4.39	<10	0.88	617	3	0.03	<1	1700	12	<5	<20	91	0.04	<10	52	<10	<1	55
73	82182	35	<0.2	1.34	5	200	<5	3.75	<1	20	14	40	3.71	<10	1.01	634	1	0.03	2	1520	8	10	<20	104	0.04	<10	38	<10	1	47
74	82183	20	<0.2	1.81	35	130	5	2.40	<1	17	13	52	5.63	<10	1.11	578	3	0.03	1	1570	14	<5	<20	74	0.04	<10	53	<10	<1	55
75	82184	20	0.2	1.63	45	545	<5	2.71	<1	43	15	74	4.62	<10	1.07	693	3	0.02	2	1820	18	<5	<20	122	0.02	<10	36	<10	<1	131
76	82185	25	0.8	1.72	75	65	<5	1.23	<1	23	11	28	4.94	<10	1.04	493	4	0.03	1	1730	18	<5	<20	40	<0.01	<10	39	<10	<1	51
77	82186	20	0.4	1.61	70	45	5	1.19	<1	21	20	35	5.17	<10	1.06	518	5	0.05	3	1710	14	<5	<20	35	<0.01	<10	55	<10	<1	32
78	82187	20	0.2	1.61	50	55	<5	2.91	<1	14	18	30	4.34	<10	1.12	592	3	0.05	<1	1850	14	<5	<20	72	0.01	<10	58	<10	1	35
79	82188	15	0.4	1.59	80	55	<5	2.44	<1	31	18	50	4.42	<10	1.04	585	3	0.05	1	1780	22	<5	<20	53	0.02	<10	54	<10	<1	49
80	82189	>1000	8.0	1.36	500	70	<5	0.34	<1	378	12	1180	>10	<10	0.63	289	31	0.01	1	980	30	<5	<20	11	0.02	40	130	<10	<1	58
81	82190	180	0.8	1.46	220	45	<5	0.47	<1	124	16	478	4.37	<10	0.91	385	4	0.02	2	1660	18	<5	<20	11	<0.01	<10	38	<10	<1	75
82	82191	60	0.8	1.32	60	50	<5	0.85	<1	16	24	127	3.78	<10	0.92	412	4	0.03	3	1810	16	<5	<20	19	<0.01	<10	36	<10	<1	48
83	82192	350	1.0	1.85	205	40	<5	1.09	<1	44	26	236	>10	<10	1.26	518	13	0.03	3	1520	34	<5	<20	27	<0.01	<10	40	<10	<1	60
84	82193	400	0.4	1.77	110	55	<5	1.48	<1	13	27	104	4.74	20	1.37	580	5	0.03	2	1760	18	<5	<20	38	<0.01	<10	43	<10	<1	50
85	82194	300	0.4	1.57	50	50	<5	1.38	<1	15	20	87	4.33	<10	1.14	642	4	0.02	1	1740	12	<5	<20	30	<0.01	<10	34	<10	<1	64
86	82195	<5	0.2	1.20	5	95	<5	3.48	<1	16	23	49	3.88	<10	0.79	651	3	0.03	2	1830	8	<5	<20	83	0.01	<10	45	<10	<1	52
87	82196	615	0.6	1.22	20	70	<5	2.59	<1	64	18	347	4.35	<10	0.82	561	3	0.03	2	1850	10	<5	<20	85	0.02	<10	53	<10	2	81
88	82197	820	0.8	1.10	55	505	<5	2.17	<1	68	14	81	2.62	<10	0.55	437	2	0.02	1	1810	10	<5	<20	58	0.02	<10	29	<10	5	289
89	82198	10	0.2																											

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1087

ECO-TECH LABORATORIES LTD.

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Bb	Sr	Sr	Tl %	U	V	W	Y	Zn	
QC/DATA:																															
<i>Repeat:</i>																															
1	82110	55	1.8	2.78	25	105	<5	7.29	1	19	37	149	6.96	<10	1.65	2344	9	0.02	15	1490	24	<5	<20	233	<0.01	<10	74	<10	<1	202	
36	82145	235	0.4	2.25	245	80	10	3.51	<1	35	35	58	5.12	<10	1.74	854	3	0.04	7	1580	18	10	<20	61	0.01	<10	143	<10	<1	55	
71	82180	255	0.4	1.61	45	80	<5	1.84	<1	15	18	82	4.52	<10	1.28	639	3	0.02	1	1770	18	<5	<20	52	0.01	<10	41	<10	<1	84	
<i>Repeat:</i>																															
1	82110	35	1.8	2.73	20	125	<5	7.03	<1	19	26	139	6.58	<10	1.59	2258	8	0.01	12	1380	18	<5	<20	228	<0.01	<10	71	<10	<1	185	
10	82119	<5	1.2	1.89	58	85	<5	3.87	<1	15	37	76	3.97	<10	0.89	893	7	0.02	33	820	14	<5	<20	94	<0.01	<10	27	<10	1	77	
19	82128	5	1.8	0.88	70	50	<5	4.79	<1	18	98	68	3.30	<10	0.45	1150	25	0.02	52	550	20	<5	<20	158	<0.01	<10	48	<10	2	33	
36	82145	280	0.6	2.05	230	75	<5	3.28	<1	33	35	53	4.75	<10	1.58	813	3	0.04	8	1410	18	<5	<20	58	0.01	<10	132	<10	<1	51	
45	82154	760	0.6	3.01	1590	50	<5	4.36	<1	121	29	158	7.01	<10	2.50	1083	6	0.04	11	1720	28	<5	<20	114	0.05	<10	227	<10	<1	108	
54	82183	10	0.8	1.99	30	55	<5	4.12	2	19	38	111	4.48	<10	1.42	1019	5	0.03	3	1030	22	8	<20	84	0.04	<10	58	<10	3	243	
71	82180	300	0.4	1.88	45	90	<5	1.79	<1	15	23	68	4.57	<10	1.24	823	3	0.02	1	1750	18	<5	<20	51	0.01	<10	43	10	<1	63	
80	82189	>1000	8.2	1.31	475	70	<5	0.34	<1	361	13	1147	>10	<10	0.61	306	30	0.01	2	850	30	<5	<20	11	0.02	30	128	<10	<1	57	
<i>Standard:</i>																															
GEO'97		130	1.2	1.78	65	150	<5	1.88	2	19	57	80	4.42	<10	0.95	709	1	0.03	22	700	24	<5	<20	80	0.08	<10	78	<10	3	76	
GEO'97		140	1.2	1.82	80	185	<5	1.81	<1	20	59	84	4.53	<10	0.97	710	<1	0.03	23	710	20	<5	<20	82	0.08	<10	79	<10	3	77	
GEO'97		-	1.4	1.88	65	170	<5	1.85	<1	21	60	88	4.63	<10	0.98	722	<1	0.03	22	730	22	<5	<20	83	0.10	<10	80	<10	3	80	

df/1097
 XLS/97Teuton
 Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

14-Oct-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK-97-1097

TEUTON RESOURCES CORPORATION
508-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 65
Sample type: ROCK
PROJECT: # NONE GIVEN
SHIPMENT: # NONE GIVEN
Samples submitted by: NOT INDICATED

Values in ppm unless otherwise reported

Table with 30 columns (Et #, Tag #, Au, Ag, Al, As, Ba, Bi, Ca, Cd, Co, Cr, Cu, Fe, La, Mg, Mn, Mo, Na, Ni, P, Pb, Sb, Sn, Sr, Ti, U, V, W, Y, Zn) and 25 rows of data.

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1097

ECO-TECH LABORATORIES LTD.

Table with 30 columns (Et #, Tag #, Au, Ag, Al, As, Ba, Bi, Ca, Cd, Co, Cr, Cu, Fe, La, Mg, Mn, Mo, Na, Ni, P, Pb, Sb, Sn, Sr, Ti, U, V, W, Y, Zn) and 19 rows of data.

41	13+50E 28+30N	40	0.6	1.71	15	50	<5	5.39	<1	35	56	1218	4.08	<10	1.49	576	1	0.04	27	2090	12	10	<20	84	0.09	<10	100	<10	7	14
42	13+50E 28+40N	60	0.6	0.80	<5	50	<5	1.02	<1	23	80	1042	3.34	<10	0.72	214	<1	0.05	17	1940	8	<5	<20	41	0.13	<10	154	<10	6	15
43	13+50E 28+50N	65	<0.2	1.71	<5	55	<5	1.12	<1	29	93	775	5.41	<10	1.71	311	<1	0.06	25	1770	14	<5	<20	39	0.21	<10	190	<10	6	34
44	13+50E 28+60N	<5	<0.2	0.73	<5	60	<5	1.08	<1	12	52	72	2.90	<10	0.45	175	<1	0.05	5	2030	8	<5	<20	45	0.10	<10	142	10	5	10
45	13+50E 28+70N	130	1.6	1.72	<5	40	<5	1.04	<1	22	104	1180	4.41	<10	1.91	432	<1	0.07	30	1710	14	<5	<20	25	0.20	<10	150	<10	7	39
46	13+50E 28+80N	120	<0.2	2.07	<5	85	<5	1.30	<1	31	106	904	5.49	<10	1.94	348	<1	0.06	30	1740	18	<5	<20	40	0.27	<10	216	<10	9	34
47	13+50E 28+90N	90	<0.2	1.88	<5	60	<5	0.95	<1	38	118	1587	5.88	<10	2.12	333	<1	0.06	35	1800	14	<5	<20	29	0.25	<10	207	<10	7	32
48	13+50E 28+00N	20	<0.2	0.73	5	50	<5	0.88	<1	18	32	181	2.40	<10	0.52	298	<1	0.06	6	1920	12	<5	<20	20	0.10	<10	111	<10	7	14
49	14+00E 23+00N	5	<0.2	2.57	<5	95	5	3.22	<1	22	73	25	5.81	10	1.64	1075	5	0.02	3	1380	18	<5	<20	50	0.02	<10	78	10	6	43
50	14+00E 23+25N	<5	<0.2	3.03	<5	225	<5	1.53	<1	40	111	427	6.68	<10	2.18	1719	8	0.01	23	1340	20	<5	<20	18	0.07	<10	115	10	1	53
51	14+00E 23+50N	10	<0.2	2.25	<5	80	<5	0.76	<1	21	50	349	4.84	<10	1.74	1153	2	0.02	10	1590	18	<5	<20	10	0.09	<10	125	<10	6	57
52	14+00E 23+75N	100	0.4	1.77	<5	50	<5	0.85	<1	35	102	1450	5.97	<10	1.93	815	1	0.04	40	1810	12	<5	<20	20	0.16	<10	279	10	7	36
53	14+00E 24+00N	125	2.6	2.34	15	135	<5	2.27	<1	48	152	2003	8.35	<10	2.05	1242	<1	0.01	39	1590	16	5	<20	31	0.17	<10	207	<10	6	62
54	14+00E 24+25N	115	<0.2	2.08	<5	80	<5	0.89	<1	43	108	1188	6.22	<10	1.99	310	<1	0.05	29	1400	18	<5	<20	34	0.34	<10	233	10	11	47
55	14+00E 24+50N	15	<0.2	2.18	<5	90	5	0.49	<1	48	114	64	7.12	<10	1.07	1735	7	0.01	18	1720	18	<5	<20	4	0.07	<10	113	10	3	27
56	14+00E 24+75N	<5	<0.2	1.03	<5	75	<5	1.02	<1	16	47	79	2.87	<10	0.47	218	<1	0.07	11	1840	14	<5	<20	31	0.13	<10	102	10	7	20
57	14+00E 25+00N	55	<0.2	2.19	<5	95	<5	0.97	<1	32	120	620	5.85	<10	2.26	481	<1	0.06	28	1430	18	<5	<20	49	0.33	<10	198	<10	11	33
58	14+00E 25+25N	20	<0.2	1.86	<5	55	<5	4.27	<1	21	43	384	4.56	<10	1.29	784	1	0.05	14	1640	12	5	<20	68	0.10	<10	157	10	4	34
59	14+00E 25+50N	<5	<0.2	1.64	<5	85	<5	0.73	<1	21	45	182	4.55	<10	1.27	596	<1	0.05	9	1890	16	5	<20	21	0.14	<10	171	10	6	35
60	14+00E 25+75N	310	0.8	1.43	<5	85	<5	1.29	<1	21	52	1338	5.49	<10	1.25	578	<1	0.06	11	2130	14	<5	<20	37	0.19	<10	216	<10	8	45

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1097

ECO-TECH LABORATORIES LTD.

El #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	TI %	U	V	W	Y	Zn		
61	14+00E 28+00N	90	0.4	1.56	15	110	<5	0.28	<1	52	88	130	6.48	<10	0.59	888	8	0.01	13	1100	12	<5	<20	4	<0.01	<10	45	<10	<1	19		
62	14+00E 28+25N	5	<0.2	2.94	<5	955	<5	0.82	<1	18	90	124	6.84	10	2.44	1135	5	0.01	29	1990	18	<5	<20	35	0.03	<10	132	10	5	50		
63	14+00E 28+50N	390	5.0	2.40	60	125	<5	0.95	1	33	57	1693	9.82	<10	1.52	1170	10	0.01	17	2240	18	<5	<20	16	<0.01	<10	151	10	<1	36		
64	14+00E 26+75N	<5	<0.2	1.39	10	130	<5	1.07	<1	14	46	56	3.53	<10	0.77	1126	1	0.01	8	1550	16	<5	<20	11	0.10	<10	79	10	8	20		
65	14+00E 27+00N	10	0.8	3.20	15	150	<5	3.27	1	36	101	203	7.65	10	2.52	1872	14	0.01	28	1580	24	<5	<20	35	0.06	<10	105	10	3	44		
QC/DATA:																																
<i>Re-split:</i>																																
R/S 1	13+00E 27+50N	310	4.2	1.42	10	65	<5	0.91	2	28	63	2196	4.28	<10	1.44	559	5	0.03	16	1850	20	5	<20	14	0.17	<10	220	10	8	102		
R/S 36	13+50E 27+80N	<5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
<i>Repeat:</i>																																
1	13+00E 27+50N	260	4.4	1.48	15	65	<5	0.90	1	28	65	2279	4.28	<10	1.47	561	11	0.03	18	1800	14	5	<20	15	0.17	<10	222	<10	8	87		
10	13+00E 28+40N	70	0.8	1.46	<5	60	<5	1.32	<1	20	78	830	3.53	<10	1.24	484	2	0.06	18	1810	12	<5	<20	34	0.13	<10	151	<10	6	36		
19	13+25E 27+70N	440	1.6	2.53	<5	75	<5	2.87	<1	38	86	1920	6.71	10	2.70	963	2	0.04	27	1900	18	<5	<20	57	0.15	<10	212	<10	6	79		
36	13+50E 27+80N	5	1.0	2.09	10	90	<5	4.13	1	17	54	189	5.36	<10	1.73	1010	1	0.04	38	2190	2	<5	<20	69	0.10	<10	236	<10	2	30		
45	13+50E 28+70N	160	1.8	1.71	<5	40	<5	1.01	<1	22	104	1195	4.42	<10	1.90	432	<1	0.06	30	1720	14	<5	<20	23	0.19	<10	148	<10	7	39		
54	14+00E 24+25N	110	<0.2	2.02	<5	75	<5	0.82	<1	41	103	1154	6.10	<10	1.85	304	<1	0.04	28	1330	16	<5	<20	30	0.30	<10	227	<10	10	48		
<i>Standard:</i>																																
GEO97		135	1.2	1.75	70	165	<5	1.84	1	21	64	84	4.39	<10	0.83	720	<1	0.03	22	720	22	10	<20	57	0.12	<10	81	<10	7	84		
GEO97		135	1.0	1.81	65	165	<5	1.84	<1	21	64	81	4.34	<10	0.98	715	<1	0.03	24	720	24	5	<20	56	0.13	<10	81	<10	7	78		

dl/1094
XLS/97Teuton
Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AK 97- 1131

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

16-Oct-97

ATTENTION: DINO CREMONESE

No. of samples received: 77

Sample type: CORE

PROJECT: # CLONE

SHIPMENT: # CL - 20

Samples submitted by: DALE ROBERTS

ET #.	Tag #	Au (g/t)	Au (oz/t)	Co (%)
3	62405	-	-	0.051
4	62406	-	-	0.058
5	62407	-	-	0.060
6	62408	-	-	0.063
7	62409	3.18	0.093	0.039
59	62461	5.84	0.170	0.040
60	62462	1.08	0.031	-
71	62473	1.60	0.047	-
72	62474	2.66	0.078	-

QC/DATA:

Standard:

STD-M	1.94	0.057	-
STD-M	1.38	0.040	-
SU-1a	-	-	0.041

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

XLS/97Teuton

Fax to Dino Vancouver 604-682-3992

15-Oct-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AK- B7- 1131

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 804-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 77
Sample type: CORE
PROJECT: # CLONE
SHIPMENT: # CL-20
Samples submitted by: DALE ROBERTS

Values in ppm unless otherwise reported

Table with 29 columns (Et.#, Tag #, Au(ppb), Ag, Al %, As, Ba, Bi, Ca %, Cd, Co, Cr, Cu, Fe %, La, Mg %, Mn, Mo, Na %, Ni, P, Pb, Sb, Sn, Sr, Ti %, U, V, W, Y, Zn) and 25 rows of data points for various sample tags.

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK- B7- 1131

ECO-TECH LABORATORIES LTD.

Table with 29 columns (Et.#, Tag #, Au(ppb), Ag, Al %, As, Ba, Bi, Ca %, Cd, Co, Cr, Cu, Fe %, La, Mg %, Mn, Mo, Na %, Ni, P, Pb, Sb, Sn, Sr, Ti %, U, V, W, Y, Zn) and 17 rows of data points for various sample tags.

42	62444	100	<0.2	1.82	45	105	<5	6.47	<1	7	11	92	3.50	<10	1.38	925	2	0.02	3	1540	8	<5	<20	120	0.02	<10	58	<10	3	84
43	62445	95	0.4	1.55	25	80	<5	5.76	1	13	21	302	3.07	<10	1.17	799	<1	0.02	1	1530	8	5	<20	87	0.04	<10	54	<10	3	110
44	62446	65	<0.2	1.70	35	65	<5	5.17	<1	11	10	127	3.21	<10	1.28	800	<1	0.02	3	1630	8	5	<20	88	0.05	<10	49	<10	3	95
45	62447	120	<0.2	1.51	45	85	<5	4.86	1	7	16	121	2.93	<10	1.19	681	<1	0.03	1	1590	16	10	<20	85	0.05	<10	67	<10	2	82
46	62448	35	<0.2	1.87	365	40	<5	3.49	21	12	11	74	3.55	<10	1.17	710	8	0.03	2	1620	68	10	<20	55	0.05	<10	49	<10	2	146
47	62449	15	<0.2	1.84	275	50	<5	2.62	<1	8	17	22	3.75	<10	1.25	677	2	0.03	1	1630	8	<5	<20	49	0.05	<10	49	<10	1	87
48	62450	350	<0.2	1.85	125	50	<5	3.81	<1	8	11	87	3.80	<10	1.48	809	<1	0.03	2	1570	24	<5	<20	84	0.05	<10	68	<10	<1	109
49	62451	75	0.2	1.61	90	95	<5	4.28	2	8	18	207	3.29	<10	1.16	791	1	0.03	2	1600	30	10	<20	75	0.05	<10	63	<10	2	127
50	62452	35	<0.2	1.42	50	165	<5	4.48	<1	13	12	79	3.02	<10	0.94	787	<1	0.03	3	1560	14	<5	<20	488	0.05	<10	45	<10	3	93
51	62453	20	<0.2	1.22	45	250	<5	4.54	<1	10	14	73	2.59	<10	0.78	705	<1	0.03	3	1600	8	5	<20	142	0.05	<10	40	<10	3	89
52	62454	65	<0.2	1.17	60	100	<5	7.43	<1	15	8	129	2.84	<10	0.75	925	1	0.02	2	1470	12	5	<20	128	0.04	<10	31	<10	2	78
53	62455	60	<0.2	1.28	30	275	<5	4.83	<1	10	13	158	2.40	<10	0.87	803	<1	0.02	3	1590	6	5	<20	97	0.04	<10	38	<10	3	97
54	62456	50	<0.2	1.12	80	60	5	6.83	<1	20	11	19	3.50	<10	0.78	1002	2	0.02	2	1500	12	5	<20	112	0.04	<10	27	<10	4	80
55	62457	105	0.8	0.96	160	60	10	7.26	3	29	18	39	8.84	<10	0.81	1048	20	0.02	1	1360	42	<5	<20	121	0.04	<10	24	<10	<1	62
56	62458	410	<0.2	1.17	90	85	<5	6.16	<1	44	9	57	2.50	<10	0.74	858	<1	0.01	2	1570	8	<5	<20	98	0.04	<10	21	<10	4	59
57	62459	80	<0.2	1.80	35	80	5	3.67	1	29	11	8	2.81	<10	1.10	759	5	0.02	8	1610	8	5	<20	71	0.03	<10	22	<10	3	75
58	62460	330	<0.2	1.65	65	115	<5	3.11	3	51	8	138	3.38	<10	1.14	748	4	0.02	14	1650	20	10	<20	81	0.02	<10	29	<10	2	97
59	62461	>1000	1.8	1.77	490	110	<5	3.72	2	400	11	101	7.90	<10	1.21	880	2	0.02	17	1290	10	10	<20	73	0.03	<10	59	<10	<1	127
60	62462	>1000	0.2	1.66	140	375	<5	7.11	<1	108	6	34	3.27	<10	1.03	1090	1	0.01	1	1500	6	5	<20	146	0.04	<10	24	<10	4	95

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1131

ECO-TECH LABORATORIES LTD.

Et #.	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
61	62463	35	<0.2	1.44	10	190	<5	4.24	3	13	16	198	2.35	<10	0.75	793	9	0.01	9	1560	8	10	<20	72	0.02	<10	22	<10	4	86
62	62464	30	<0.2	1.13	40	685	<5	5.39	3	31	8	8	2.08	<10	0.82	732	7	0.02	8	1650	4	5	<20	125	0.02	<10	21	<10	5	85
63	62465	10	<0.2	1.44	5	980	<5	4.45	3	6	13	20	2.87	<10	0.96	740	9	0.02	11	1600	12	5	<20	128	0.02	<10	32	<10	3	77
64	62466	25	<0.2	1.24	10	160	<5	3.59	2	13	9	241	2.63	<10	0.77	855	8	0.03	8	1640	18	10	<20	80	0.02	<10	32	<10	3	72
65	62467	20	<0.2	1.09	20	205	<5	3.15	3	20	14	359	2.65	<10	0.65	587	7	0.03	10	1640	14	5	<20	78	<0.01	<10	28	<10	1	76
66	62468	10	<0.2	1.46	15	105	<5	3.56	3	17	9	17	2.76	<10	0.91	649	5	0.01	11	1580	18	5	<20	64	<0.01	<10	22	<10	2	87
67	62469	245	<0.2	1.14	50	145	<5	4.07	4	48	14	100	3.21	<10	0.66	683	4	0.01	14	1560	20	10	<20	85	0.01	<10	28	<10	2	90
68	62470	15	<0.2	0.73	10	90	5	3.89	3	12	11	20	3.54	<10	0.25	503	3	0.01	2	1590	14	<5	<20	81	0.03	<10	25	<10	2	62
69	62471	70	0.2	0.87	40	130	<5	2.81	<1	33	15	78	2.58	<10	0.20	387	2	0.01	<1	1650	22	<5	<20	84	0.03	<10	27	<10	2	32
70	62472	30	0.4	1.39	45	100	<5	3.29	<1	22	11	122	3.30	<10	0.82	681	5	0.02	2	1630	48	<5	<20	88	<0.01	<10	30	<10	1	80
71	62473	>1000	2.2	1.84	20	85	<5	1.34	2	26	10	374	5.09	<10	1.18	529	4	0.02	3	1470	82	<5	<20	31	<0.01	<10	31	<10	<1	105
72	62474	>1000	5.4	2.04	70	55	<5	0.66	<1	41	17	777	9.02	<10	1.23	599	9	0.01	5	1210	34	<5	<20	16	<0.01	<10	43	<10	<1	130
73	62475	35	0.4	1.64	30	70	<5	2.30	<1	13	14	103	3.92	<10	1.17	811	8	0.03	2	1890	20	<5	<20	58	<0.01	<10	43	<10	<1	79
74	62476	25	0.4	1.58	25	80	<5	3.79	<1	12	18	63	3.41	<10	1.05	828	2	0.03	2	1690	18	<5	<20	82	0.01	<10	40	<10	2	77
75	62477	5	<0.2	1.63	20	100	<5	4.42	1	13	11	43	3.16	<10	1.02	774	1	0.02	2	1890	8	<5	<20	91	0.02	<10	28	<10	1	109
76	62478	10	0.4	1.36	25	330	<5	4.49	<1	10	13	61	2.83	<10	0.84	685	2	0.02	3	1640	16	<5	<20	100	0.01	<10	29	<10	2	74
77	62479	5	0.2	1.53	15	65	<5	3.31	<1	14	12	75	3.46	<10	0.92	621	3	0.03	3	1670	18	<5	<20	73	<0.01	<10	39	<10	<1	80

QC/DATA:

Repeat:																															
R/S 1	62403	40	<0.2	2.83	15	60	5	2.89	1	64	21	55	9.72	<10	2.67	1575	3	0.03	13	1890	18	<5	<20	36	0.12	<10	174	<10	<1	138	
R/S 36	62438	15	<0.2	1.92	20	50	<5	4.32	<1	10	15	27	4.17	<10	1.35	683	2	0.03	3	1600	14	<5	<20	82	0.02	<10	81	<10	3	102	
R/S 71	62473	>1000	2.0	1.85	25	85	<5	1.38	1	24	8	339	5.04	<10	1.18	528	4	0.02	2	1500	80	<5	<20	29	<0.01	<10	32	<10	<1	107	

Repeat:																															
1	62403	55	<0.2	2.99	15	85	15	2.70	2	65	21	58	9.80	<10	2.79	1625	3	0.04	13	1870	18	<5	<20	37	0.11	<10	177	<10	<1	136	
10	62412	20	<0.2	2.42	15	465	<5	3.55	4	31	23	255	8.59	<10	2.08	1157	3	0.03	7	2150	20	<5	<20	58	0.12	<10	136	<10	<1	82	
19	62421	35	<0.2	1.68	10	55	<5	2.47	<1	13	16	41	3.85	<10	1.33	703	2	0.04	2	1640	6	<5	<20	52	0.03	<10	61	<10	2	45	
36	62438	15	<0.2	1.97	25	60	<5	4.41	<1	10	19	27	4.06	<10	1.34	970	2	0.04	3	1590	14	<5	<20	85	0.02	<10	62	<10	3	91	
45	62447	100	<0.2	1.46	45	60	<5	4.73	1	7	16	123	2.85	<10	1.15	662	<1	0.03	2	1540	18	10	<20	81	0.06	<10	66	<10	2	80	
54	62456	55	<0.2	1.12	85	85	<5	6.99	2	20	12	18	3.57	<10	0.77	1022	4	0.02	2	1540	12	5	<20	114	0.02	<10	28	<10	3	85	
71	62473	-	2.2	1.87	30	90	<5	1.33	2	26	10	368	5.08	<10	1.18	524	4	0.02	2	1520	64	<5	<20	28	<0.01	<10	32	<10	<1	106	

Standard:																															
GEO'97		135	1.2	1.71	85	180	<5	1.78	<1	19	59	78	4.35	<10	0.96	699	<1	0.03	20												

CERTIFICATE OF ASSAY AK 97- 1132

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

14-Oct-97

ATTENTION: DINO CREMONESE

No. of samples received: 12

Sample type: CORE

PROJECT: # CLONE

SHIPMENT: # Not Given

Samples submitted by: DALE ROBERTS

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Zn (%)
2	DC 97 61	3.70	0.108	-	-	-	-
6	DC 97 65	-	-	172.8	5.04	1.53	-
8	DC 97 67	-	-	-	-	-	2.86

QC/DATA:

Standard:

CPb-1	-	-	-	-	-	0.25	4.42
Mp-IA	-	-	69.7	2.03	1.44	-	-
STD-M	1.94	0.057	-	-	-	-	-

XLS/97Teuton

Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

14-Oct-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KANLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 97-1132

TEUTON RESOURCES CORPORATION
508-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

Phone: 604-573-5700
Fax : 604-573-4557

No. of samples received: 12
Sample type: CORE
PROJECT: # GLONE
SHIPMENT: # Not Given
Samples submitted by: DALE ROBERTS

Values in ppm unless otherwise reported

El#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	DC 97 60	15	<0.2	3.49	<5	40	10	2.51	<1	89	188	40	8.27	<10	4.08	1148	<1	0.04	52	1620	4	<5	<20	52	0.17	<10	219	<10	<1	57
2	DC 97 61	>1000	17.8	0.36	110	80	<5	0.30	<1	19	1	1217	>10	<10	0.28	217	37	0.01	2	<10	12	<5	<20	<1	0.03	10	78	<10	<1	24
3	DC 97 62	130	0.8	3.35	65	80	<5	7.81	<1	38	168	860	8.61	<10	3.61	1891	1	0.03	39	1670	6	<5	<20	74	0.15	<10	271	10	<1	59
4	DC 97 63	10	<0.2	1.57	<5	1125	<5	6.88	<1	5	27	14	4.34	<10	0.89	1731	3	0.01	<1	1410	8	<5	<20	103	0.02	<10	38	<10	5	35
5	DC 97 64	35	<0.2	2.80	10	50	<5	1.81	<1	28	129	510	8.25	<10	2.77	985	2	0.04	41	2020	10	<5	<20	24	0.12	<10	171	10	<1	43
6	DC 97 65	75	>30	2.21	10	185	<5	2.37	2	39	48	>10000	2.87	<10	1.84	1490	1	0.02	8	540	38	30	<20	89	0.01	<10	32	<10	1	320
7	DC 97 66	35	0.6	1.95	130	70	<5	9.01	<1	17	17	54	6.06	<10	1.04	1246	5	0.01	4	1000	12	<5	<20	125	<0.01	<10	50	<10	<1	93
8	DC 97 67	775	12.8	0.38	8325	15	<5	0.12	175	17	62	224	6.80	<10	0.13	69	<1	0.01	18	280	200	15	<20	3	<0.01	10	12	<10	<1	>10000
9	DC 97 68	110	<0.2	1.37	15	80	<5	1.19	1	19	81	780	3.32	<10	1.35	313	<1	0.06	25	1540	4	<5	<20	43	0.12	<10	111	<10	<1	70
10	DC 97 69	15	<0.2	3.74	25	55	10	5.34	<1	37	135	19	7.38	<10	3.21	1041	5	0.03	55	2960	6	<5	<20	165	<0.01	<10	202	<10	4	79
11	DC 97 70	10	<0.2	2.46	<5	310	<5	9.33	2	21	80	120	7.50	<10	3.51	1175	8	0.01	35	1670	2	<5	<20	287	<0.01	<10	105	<10	4	51
12	DC 97 67X	100	0.6	1.50	<5	55	<5	1.18	<1	25	79	762	4.47	<10	1.47	348	10	0.06	32	1710	8	<5	<20	35	0.15	<10	111	<10	<1	28

QC DATA:

Resplit:																															
R/S 1	DC 97 60	15	<0.2	3.31	<5	30	10	2.42	<1	82	170	38	7.90	<10	3.66	1098	2	0.04	51	1610	6	<5	<20	48	0.14	<10	209	<10	<1	56	
Repeat:																															
1	DC 97 60	20	<0.2	3.44	<5	35	10	2.47	<1	86	167	45	8.13	<10	4.00	1134	<1	0.04	53	1680	6	<5	<20	51	0.16	<10	215	<10	<1	59	
Standard:																															
GEO97		-	1.2	1.75	65	145	<5	1.82	<1	18	64	77	3.89	<10	0.98	848	<1	0.03	22	680	18	<5	<20	63	0.12	<10	78	<10	3	68	

df/1120
XLS/97

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc. T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AK 97- 1127

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

16-Oct-97

ATTENTION: DINO CREMONESE

No. of samples received: 70

Sample type: CORE

PROJECT: # CLONE

SHIPMENT: # CL-21

Samples submitted by: DALE ROBERTS

ET #.	Tag #	Au (g/t)	Au (oz/t)	Co (%)
1	62480	2.48	0.072	-
4	62483	-	-	0.026
24	66003	1.31	0.038	-
43	66022	1.76	0.051	-
59	66038	1.75	0.051	-

QC/DATA:

Standard:

STD-M	1.41	0.041	-
Su-la	-	-	0.041

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

XLS/97Teuton

Fax to Dino Vancouver 604-682-3992

15-Oct-87

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 87- 1127

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

Phone: 804-573-5700
Fax : 604-573-4557

No. of samples received: 70
Sample type: CORE
PROJECT: # CLONE
SHIPMENT: # CL-21
Samples submitted by: DALE ROBERTS

Values in ppm unless otherwise reported

Et.#	Tag #	Au(ppb)	Ag	Al%	As	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	TI%	U	V	W	Y	Zn
1	62480	>1000	<0.2	1.37	55	95	<5	1.43	2	74	32	82	4.91	<10	0.99	681	2	0.03	5	1470	26	<5	<20	31	0.06	<10	79	<10	<1	596
2	62481	85	<0.2	2.56	35	120	10	0.78	<1	82	18	72	9.23	<10	2.26	1195	3	0.02	11	1970	18	<5	<20	20	0.13	<10	142	<10	<1	485
3	62482	200	<0.2	2.23	30	125	<5	2.16	1	83	30	118	8.29	<10	1.95	1286	4	0.03	12	1530	18	<5	<20	52	0.12	<10	164	<10	<1	334
4	62483	260	<0.2	1.64	50	550	<5	4.03	2	224	23	83	7.85	<10	1.29	1103	2	0.02	13	1560	18	<5	<20	82	0.13	<10	158	<10	<1	434
5	62484	35	0.2	1.32	60	110	<5	5.73	3	82	28	77	4.01	<10	0.96	1190	3	0.03	3	1470	10	10	<20	71	0.06	<10	100	<10	2	219
6	62485	40	0.6	1.32	80	90	<5	0.49	2	81	18	177	3.82	<10	0.87	666	3	0.03	2	1540	14	5	<20	11	0.02	<10	86	<10	<1	237
7	62486	20	0.2	1.71	25	85	<5	1.15	<1	44	32	186	3.96	<10	1.26	770	3	0.03	3	1610	12	5	<20	26	0.04	<10	68	<10	<1	156
8	62487	15	<0.2	1.63	15	85	<5	2.16	<1	21	25	197	3.82	<10	1.30	714	<1	0.04	2	1870	8	<5	<20	53	0.06	<10	84	<10	<1	79
9	62488	20	<0.2	1.41	10	70	<5	2.81	5	23	32	183	3.97	<10	1.07	681	4	0.06	3	1550	22	<5	<20	69	0.07	<10	109	<10	<1	47
10	62489	35	<0.2	3.68	25	80	<5	2.58	2	43	17	320	>10	<10	3.23	1504	5	0.04	20	1920	18	<5	<20	43	0.17	<10	229	<10	<1	86
11	62490	25	<0.2	3.56	30	75	<5	3.23	1	43	18	315	>10	<10	3.27	1397	5	0.03	22	1740	10	<5	<20	50	0.16	<10	235	<10	<1	63
12	62491	10	<0.2	4.02	<5	85	<5	3.21	<1	40	17	189	>10	<10	3.78	1376	3	0.03	20	1830	12	<5	<20	84	0.15	<10	248	<10	<1	87
13	62492	20	<0.2	3.08	15	65	<5	5.35	<1	33	19	85	7.84	<10	2.93	1168	1	0.03	11	1990	14	<5	<20	76	0.16	<10	186	<10	<1	46
14	62493	30	<0.2	3.21	25	70	<5	4.33	<1	33	21	365	9.37	<10	2.84	1208	2	0.02	17	1870	10	<5	<20	84	0.17	<10	199	<10	<1	62
15	62494	585	<0.2	3.33	40	280	<5	3.10	1	35	18	321	>10	<10	3.12	1070	4	0.02	15	1720	14	<5	<20	64	0.17	<10	245	<10	<1	73
16	62495	55	<0.2	2.99	15	125	<5	2.38	<1	31	20	197	9.54	<10	2.68	870	3	0.02	14	2030	24	<5	<20	54	0.11	<10	182	<10	<1	101
17	62496	35	<0.2	3.74	10	100	<5	4.16	<1	23	33	209	9.49	<10	3.51	1160	5	0.03	17	2030	24	<5	<20	84	0.13	<10	218	<10	<1	84
18	62497	340	0.6	3.53	60	125	<5	4.58	7	90	45	475	8.98	<10	3.09	1262	5	0.03	15	1750	42	<5	<20	97	0.12	<10	177	<10	<1	344
19	62498	150	<0.2	2.43	95	300	<5	6.85	8	92	16	109	8.38	<10	1.88	1066	3	0.01	9	1870	12	<5	<20	100	0.05	<10	93	<10	2	471
20	62499	120	0.2	2.21	105	95	<5	4.01	3	65	16	127	5.10	<10	1.66	1054	3	0.02	5	1600	14	<5	<20	89	0.03	<10	58	<10	2	244

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS AK 97- 1127

ECO-TECH LABORATORIES LTD.

Et.#	Tag #	Au(ppb)	Ag	Al%	As	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	TI%	U	V	W	Y	Zn
21	66500	50	<0.2	3.86	35	80	<5	5.20	<1	47	10	143	8.26	<10	2.75	1472	5	0.02	8	1930	16	<5	<20	85	0.05	<10	109	<10	1	215
22	66001	115	0.8	2.18	210	95	<5	4.81	<1	173	18	181	5.50	<10	1.53	1012	5	0.02	2	1580	14	<5	<20	77	0.02	<10	73	<10	2	160
23	66002	95	0.4	1.84	210	70	<5	4.51	<1	169	28	150	3.52	<10	1.29	877	3	0.02	1	1530	10	<5	<20	80	0.02	<10	61	<10	2	113
24	66003	>1000	1.0	4.07	120	85	<5	4.17	<1	46	21	809	9.88	<10	3.45	1279	32	0.03	12	2090	46	<5	<20	87	0.13	<10	223	<10	<1	105
25	66004	30	<0.2	3.84	65	65	<5	4.29	<1	38	28	238	9.51	<10	3.39	1102	12	0.03	13	1990	16	<5	<20	93	0.11	<10	268	<10	<1	53
26	66005	140	<0.2	3.42	90	55	<5	5.17	<1	83	42	184	8.03	<10	2.98	1228	3	0.03	12	1770	18	<5	<20	101	0.11	<10	203	<10	<1	69
27	66006	20	<0.2	1.74	15	50	<5	3.13	<1	14	27	110	3.97	<10	1.37	683	2	0.05	3	1580	10	<5	<20	69	0.05	<10	98	<10	2	48
28	66007	10	<0.2	1.85	15	55	5	2.89	<1	9	21	24	3.82	<10	1.43	669	3	0.06	3	1630	12	<5	<20	71	0.04	<10	88	<10	3	81
29	66008	5	<0.2	2.07	10	70	5	2.19	<1	8	26	8	3.80	<10	1.65	605	<1	0.05	<1	1640	8	<5	<20	47	0.08	<10	73	<10	3	80
30	66009	5	<0.2	2.04	20	55	<5	2.27	<1	10	23	22	4.14	<10	1.81	625	2	0.05	<1	1610	12	<5	<20	59	0.06	<10	95	<10	2	82
31	66010	5	<0.2	2.00	15	85	5	2.01	<1	11	19	24	3.70	<10	1.83	555	<1	0.04	<1	1800	10	<5	<20	56	0.05	<10	73	<10	2	52
32	66011	5	<0.2	1.91	20	65	<5	1.98	<1	9	20	26	3.46	<10	1.52	489	<1	0.05	1	1600	10	5	<20	80	0.09	<10	64	<10	2	35
33	66012	5	<0.2	1.80	15	90	<5	2.19	<1	8	27	29	3.30	<10	1.41	511	<1	0.06	2	1610	8	5	<20	84	0.08	<10	71	<10	2	36
34	66013	5	<0.2	1.88	20	70	5	2.48	<1	8	24	25	3.89	<10	1.49	581	2	0.06	2	1650	12	10	<20	50	0.08	<10	101	<10	2	38
35	66014	35	<0.2	1.90	35	80	5	2.90	<1	18	18	21	3.85	<10	1.43	681	<1	0.04	2	1580	10	<5	<20	57	0.07	<10	68	<10	2	40
36	66015	20	<0.2	2.04	80	70	<5	3.55	<1	16	16	36	3.79	<10	1.31	811	2	0.04	3	1580	8	5	<20	58	0.05	<10	53	<10	4	47
37	66016	5	<0.2	2.08	85	80	<5	3.22	<1	13	15	18	4.08	<10	1.47	749	1	0.04	1	1580	10	<5	<20	58	0.06	<10	58	<10	3	44
38	66017	85	<0.2	1.94	50	85	<5	2.78	<1	47	21	42	3.55	<10	1.25	817	3	0.03	2	1840	8	5	<20	52	0.02	<10	42	<10	2	48
39	66018	540	<0.2	1.83	85	100	<5	3.85	<1	57	17	118	3.17	<10	0.96	820	2	0.03	1	1820	8	5	<20	74	0.02	<10	34	<10	2	86

40	66019	15	<0.2	1.72	15	90	<5	4.22	<1	11	15	58	3.27	<10	1.15	683	3	0.03	2	1590	8	5	<20	88	0.05	<10	39	<10	4	35
41	66020	10	<0.2	1.75	25	85	<5	3.84	<1	12	17	74	3.58	<10	1.13	718	4	0.03	<1	1830	8	<5	<20	87	0.07	<10	38	<10	4	37
42	66021	10	<0.2	1.77	15	85	<5	3.08	<1	12	22	78	3.94	<10	1.08	843	8	0.04	<1	1820	10	<5	<20	58	0.06	<10	47	<10	2	46
43	66022	>1000	<0.2	1.74	80	85	<5	3.55	<1	48	38	89	3.88	<10	1.12	897	5	0.03	3	1250	8	5	<20	86	0.07	<10	45	<10	5	114
44	66023	80	<0.2	1.53	75	80	<5	4.01	<1	75	42	84	3.50	<10	1.02	890	11	0.04	2	990	12	<5	<20	82	0.08	<10	43	<10	8	79
45	66024	150	<0.2	1.54	25	105	<5	2.87	2	16	31	148	3.36	<10	1.02	579	8	0.04	2	1830	14	<5	<20	57	0.03	<10	45	<10	3	167
46	66025	145	<0.2	1.45	35	105	<5	3.65	1	11	27	87	3.17	<10	0.95	600	11	0.05	2	1820	22	5	<20	60	0.03	<10	51	<10	3	121
47	66026	45	<0.2	1.61	25	70	<5	3.31	<1	12	28	69	3.41	<10	1.08	828	18	0.05	2	1640	20	<5	<20	59	0.06	<10	53	<10	3	113
48	66027	115	<0.2	1.84	25	115	<5	2.73	1	12	23	58	3.72	<10	1.25	802	5	0.05	<1	1510	14	<5	<20	52	0.07	<10	58	<10	4	95
49	66028	5	<0.2	1.96	20	255	5	2.82	<1	10	24	35	3.83	<10	1.53	589	5	0.06	2	1650	10	10	<20	69	0.09	<10	61	<10	3	73
50	66029	10	<0.2	2.00	25	130	<5	3.09	1	11	16	48	3.94	<10	1.58	634	2	0.06	2	1680	14	5	<20	86	0.08	<10	58	<10	3	61
51	66030	5	<0.2	2.19	15	95	10	2.11	1	12	23	22	4.34	<10	1.74	641	1	0.06	1	1870	14	<5	<20	44	0.07	<10	55	<10	4	88
52	66031	90	<0.2	1.81	55	175	<5	2.77	2	52	14	106	3.44	<10	1.16	578	3	0.05	<1	1840	10	5	<20	47	0.03	<10	35	<10	3	90
53	66032	10	<0.2	1.60	85	85	<5	2.91	<1	67	20	102	3.17	<10	0.99	540	3	0.03	<1	1850	12	5	<20	49	0.03	<10	30	<10	3	83
54	66033	235	<0.2	1.98	160	105	<5	2.18	<1	145	19	452	4.88	<10	1.19	589	5	0.03	2	1530	10	<5	<20	38	0.04	<10	39	<10	1	97
55	66034	35	<0.2	1.82	35	125	<5	3.84	<1	29	22	104	3.33	<10	1.28	643	<1	0.04	<1	1570	10	5	<20	73	0.06	<10	40	<10	4	50

ICP CERTIFICATE OF ANALYSIS AK 97-1127

ECO-TECH LABORATORIES LTD.

TEUTON RESOURCES CORPORATION

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fa %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
56	66035	35	<0.2	1.90	85	140	<5	2.60	<1	61	18	150	3.70	<10	1.28	585	2	0.03	<1	1580	10	5	<20	52	0.05	<10	38	<10	3	74
57	66036	25	<0.2	1.84	45	105	<5	3.23	<1	40	20	130	3.49	<10	0.93	603	2	0.03	<1	1630	10	<5	<20	61	0.02	<10	35	<10	2	52
58	66037	10	<0.2	1.90	70	120	<5	2.89	<1	59	23	123	3.79	<10	1.12	612	3	0.03	2	1610	12	<5	<20	50	0.03	<10	41	<10	3	72
59	66038	>1000	1.6	1.91	150	170	<5	3.61	<1	137	20	362	5.78	<10	1.10	708	5	0.02	2	1430	16	<5	<20	78	0.03	<10	45	<10	<1	101
60	66039	95	0.4	1.78	65	85	<5	4.28	<1	33	15	218	4.06	<10	1.01	754	4	0.03	2	1590	14	<5	<20	80	0.02	<10	38	<10	1	77
61	66040	35	0.4	1.87	90	95	<5	3.84	<1	22	21	173	4.15	<10	1.08	747	5	0.03	1	1820	18	<5	<20	63	0.02	<10	42	<10	1	79
62	66041	230	0.4	1.47	205	85	<5	4.86	<1	26	24	107	3.98	<10	0.75	733	11	0.03	1	1410	14	<5	<20	82	0.02	<10	39	<10	2	59
63	66042	5	<0.2	1.94	35	75	<5	5.49	<1	19	23	81	3.88	<10	1.28	1082	8	0.03	1	1520	14	<5	<20	86	0.03	<10	43	<10	4	87
64	66043	5	<0.2	1.94	35	70	<5	9.43	<1	19	15	74	3.57	<10	1.29	1375	8	0.02	<1	1430	14	10	<20	142	0.04	<10	38	<10	8	73
65	66044	5	<0.2	2.00	30	90	<5	5.59	<1	20	20	71	3.90	<10	1.38	945	8	0.03	1	1500	16	10	<20	84	0.06	<10	44	<10	4	82
66	66045	5	<0.2	1.85	35	70	<5	4.91	<1	18	19	72	3.73	<10	1.25	888	8	0.02	2	1410	16	10	<20	79	0.03	<10	40	<10	3	84
67	66046	5	0.4	1.81	85	55	<5	2.88	<1	26	23	120	4.11	<10	1.22	858	8	0.02	1	1320	22	10	<20	53	0.01	<10	43	<10	1	80
68	66047	5	0.2	1.80	50	85	<5	3.91	5	15	22	77	4.19	<10	1.11	932	9	0.04	<1	1600	18	<5	<20	82	0.02	<10	50	<10	1	113
69	66048	5	0.8	1.90	70	75	<5	3.89	<1	18	23	109	4.41	<10	1.13	1028	8	0.03	3	1510	72	<5	<20	88	0.03	<10	44	<10	4	84
70	66049	5	0.8	1.81	60	80	<5	3.77	<1	31	17	133	3.99	<10	0.89	948	13	0.03	<1	1580	26	<5	<20	70	0.03	<10	38	<10	4	76

QC DATA:

Repeat:																															
R/S 1	62480	>1000	<0.2	1.33	45	95	<5	1.51	2	74	35	58	4.90	<10	0.95	670	2	0.03	5	1520	24	<5	<20	30	0.07	<10	78	<10	1	805	
R/S 36	66015	15	<0.2	1.91	90	60	<5	3.38	<1	17	18	38	3.85	<10	1.27	602	1	0.03	1	1650	10	<5	<20	52	0.05	<10	50	20	4	50	
Repeat:																															
1	82480	>1000	<0.2	1.37	60	90	<5	1.47	2	77	34	85	5.08	<10	1.01	688	3	0.02	5	1530	28	<5	<20	29	0.08	<10	80	<10	<1	827	
10	82489	30	<0.2	3.87	15	75	15	2.58	2	42	18	321	>10	<10	3.26	1501	8	0.04	20	1910	16	<5	<20	41	0.14	<10	221	<10	<1	83	
19	82498	145	<0.2	2.41	85	280	<5	6.86	9	91	17	107	6.33	<10	1.82	1084	3	0.01	10	1860	14	5	<20	96	0.05	<10	92	<10	2	478	
36	66015	20	<0.2	2.04	100	70	<5	3.81	<1	17	18	38	3.86	<10	1.31	828	2	0.04	<1	1810	12	<5	<20	58	0.05	<10	53	<10	4	49	
45	66024	150	0.2	1.50	20	100	<5	2.83	3	17	30	141	3.33	<10	1.00	572	7	0.04	2	1810	14	<5	<20	54	0.03	<10	43	<10	3	167	
54	66033	165	0.2	1.83	150	95	<5	2.22	<1	143	19	453	4.93	<10	1.18	578	5	0.02	1	1570	12	<5	<20	38	0.04	<10	38	<10	<1	97	
Standard:																															
GE097		130	1.2	1.79	60	155	<5	1.78	<1	20	81	82	4.22	<10	0.96	888	<1	0.03	24	680	20	<5	<20	62	0.12	<10	80	<10	5	79	
GE097		125	1.2	1.70	60	155	<5	1.77	<1	20	60	78	4.16	<10	0.96	889	<1	0.03	25	870	24	<5	<20	58	0.12	<10	77	<10	4	78	

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

dl/1127
XLS/97

CERTIFICATE OF ASSAY AK 97- 1128

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

15-Oct-97

ATTENTION: DINO CREMONESE

No. of samples received: 28
Sample type: CORE
PROJECT: # CLONE
SHIPMENT: # Not Given
Samples submitted by: DALE ROBERTS

ET #.	Tag #	Au (g/t)	Au (oz/t)
24	62377	7.10	0.207

QC/DATA:

Standard:
STD-M

1.94 0.057

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

XLS/97 Teuton
Fax to Dino Vancouver 604-682-3992

15-Oct-97

ICP CERTIFICATE OF ANALYSIS AK 87-1128

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

TEUTON RESOURCES CORPORATION
508-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DRINO CREMONESE

No. of samples received: 28
Sample type: CORE
PROJECT: # CLONE
SHIPMENT: # Not Given
Samples submitted by: DALE ROBERTS

Values in ppm unless otherwise reported

Et#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	62298	25	1.2	5.18	90	100	<5	4.53	<1	31	28	58	>10	<10	4.74	1490	7	0.03	13	2080	8	<5	<20	222	0.01	<10	291	<10	<1	131
2	62299	115	1.8	4.47	70	95	<5	4.29	<1	38	28	121	9.28	<10	4.03	1515	9	0.02	11	1840	20	<5	<20	184	<0.01	<10	131	<10	<1	199
3	62300	115	0.8	3.80	20	110	<5	4.87	1	21	28	48	8.40	<10	2.58	2348	8	0.02	7	1390	24	<5	<20	153	<0.01	<10	131	<10	<1	182
4	62301	20	<0.2	4.27	10	130	10	5.11	<1	18	25	25	9.17	<10	2.83	2402	7	0.02	8	1510	14	<5	<20	175	0.01	<10	155	<10	<1	182
5	62302	25	<0.2	3.11	5	120	10	6.70	<1	13	13	2	8.00	<10	2.27	1605	4	0.03	2	1490	8	<5	<20	212	<0.01	<10	117	<10	<1	119
6	62303	25	<0.2	2.82	10	140	10	5.57	<1	13	28	2	5.40	<10	2.08	1318	8	0.04	3	1480	8	<5	<20	171	<0.01	<10	104	<10	<1	127
7	62304	80	<0.2	3.42	15	140	<5	5.62	<1	16	18	2	6.60	<10	2.58	1385	4	0.04	5	1530	10	<5	<20	162	<0.01	<10	132	<10	<1	170
8	62340	10	1.0	2.94	20	210	<5	>10	3	24	41	137	5.92	<10	2.01	1851	5	0.01	13	1690	32	5	<20	482	<0.01	<10	77	<10	<1	178
9	62341	5	0.8	3.18	30	200	<5	>10	3	28	28	92	8.34	<10	2.14	1777	5	0.01	12	1940	26	5	<20	223	<0.01	<10	101	<10	<1	183
10	62342	5	0.6	3.25	30	260	<5	9.04	1	28	48	109	8.55	<10	2.18	1851	5	0.01	15	1920	14	<5	<20	286	<0.01	<10	91	<10	<1	130
11	62343	10	0.8	2.32	25	320	<5	>10	<1	21	89	81	4.73	<10	1.43	1877	3	0.01	23	1010	10	<5	<20	282	<0.01	<10	69	<10	<1	101
12	62344	10	1.4	3.58	40	160	<5	8.18	<1	27	73	218	6.68	<10	2.58	1672	5	0.01	17	1620	10	<5	<20	219	<0.01	<10	101	<10	<1	115
13	62345	15	1.2	2.75	35	170	<5	>10	<1	20	34	90	5.58	<10	1.87	1806	5	0.01	9	1530	10	<5	<20	338	<0.01	<10	85	<10	2	109
14	62346	35	3.0	2.69	45	105	<5	7.47	9	31	33	207	6.50	<10	1.99	1578	7	0.01	14	1810	36	5	<20	188	<0.01	<10	78	<10	<1	573
15	62361	110	0.4	3.37	30	120	10	6.39	<1	20	33	83	7.66	<10	3.20	1286	6	0.03	12	1690	10	<5	<20	175	0.01	<10	243	<10	2	47
16	62362	450	0.6	3.83	55	110	5	5.09	<1	25	35	89	8.54	<10	3.39	1193	11	0.04	15	1780	10	<5	<20	119	0.01	<10	308	<10	<1	57
17	62363	375	<0.2	3.42	20	225	5	8.10	<1	18	38	30	8.47	<10	3.01	1418	8	0.03	7	1680	8	<5	<20	188	0.07	<10	277	<10	4	49
18	62364	35	<0.2	3.20	25	80	10	5.20	<1	19	38	31	7.96	<10	2.95	1091	3	0.04	11	1830	8	<5	<20	121	0.09	<10	268	10	2	51
19	62365	20	<0.2	3.47	25	120	15	4.78	<1	18	35	18	8.25	<10	3.33	1081	3	0.04	12	1880	8	<5	<20	138	0.08	<10	278	<10	<1	58
20	62366	15	<0.2	3.78	45	450	10	4.35	<1	36	38	13	7.84	<10	3.90	1178	4	0.04	13	1900	8	<5	<20	85	0.03	<10	286	<10	1	63

ICP CERTIFICATE OF ANALYSIS AK 87-1128

ECO-TECH LABORATORIES LTD.

TEUTON RESOURCES CORPORATION

Et#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
21	62367	15	<0.2	3.46	40	245	5	5.23	<1	32	37	17	7.58	<10	3.46	1239	5	0.04	12	1740	10	<5	<20	103	0.03	<10	284	<10	<1	58
22	62375	10	<0.2	3.77	10	85	5	5.33	<1	17	41	38	8.44	<10	3.76	1239	2	0.04	9	1630	14	<5	<20	143	0.10	<10	272	<10	<1	87
23	62376	175	<0.2	4.14	15	170	10	4.17	<1	21	36	76	9.49	<10	4.04	1104	11	0.05	12	1800	16	<5	<20	102	0.11	<10	276	<10	<1	60
24	62377	>1000	0.4	3.81	10	60	<5	8.11	<1	18	35	118	8.73	<10	3.77	1173	39	0.04	12	1760	10	<5	<20	167	0.13	<10	278	<10	<1	63
25	62378	205	<0.2	3.88	25	130	5	5.04	<1	24	42	128	8.37	<10	3.59	1036	5	0.05	18	1700	26	<5	<20	134	0.08	<10	262	<10	<1	99
26	62379	85	<0.2	3.55	25	80	<5	4.82	<1	23	39	52	8.03	<10	3.47	1021	3	0.05	11	1720	16	<5	<20	108	0.09	<10	260	<10	1	91
27	62380	20	<0.2	3.54	10	50	10	5.20	<1	18	42	42	7.73	<10	3.48	1013	4	0.05	11	1720	14	<5	<20	141	0.05	<10	285	<10	<1	116
28	62381	10	<0.2	3.63	10	175	<5	4.85	<1	16	41	74	8.05	<10	3.62	1015	4	0.05	12	1780	14	<5	<20	130	0.06	<10	289	<10	<1	94

QC DATA:

Repeat:
R/S 1 62298 30 1.4 5.09 55 110 10 4.78 <1 34 23 54 >10 <10 4.62 1517 6 0.03 15 2130 10 <5 <20 226 0.01 <10 292 <10 <1 136

Repeat:
1 62298 25 1.2 5.08 55 95 10 4.52 <1 34 26 55 >10 <10 4.68 1479 7 0.02 14 2070 10 <5 <20 217 0.01 <10 288 <10 <1 140
10 62342 5 0.8 3.21 30 275 <5 9.11 1 26 48 106 8.83 <10 2.15 1892 4 0.01 14 1970 18 <5 <20 275 <0.01 <10 91 <10 <1 137
19 62365 20 <0.2 3.48 30 135 10 4.75 <1 19 35 17 8.20 <10 3.29 1072 3 0.06 11 1860 10 <5 <20 137 0.08 <10 277 <10 <1 58

Standard:
GEO97 140 1.2 1.78 85 155 <5 1.78 <1 19 59 77 4.35 <10 0.96 892 <1 0.03 22 880 22 <5 <20 58 0.11 <10 79 <10 5 71

CERTIFICATE OF ASSAY AK 97- 1129

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

14-Oct-97

ATTENTION: DINO CREMONESE

No. of samples received: 14

Sample type: CORE

PROJECT: # CLONE

SHIPMENT: # Not Given

Samples submitted by: DALE ROBERTS

<u>ET #.</u>	<u>Tag #</u>	<u>Au (g/t)</u>	<u>Au (oz/t)</u>
9	MM-97-25	12.70	0.370
10	MM-97-26	2.66	0.078

QC/DATA:

Standard:

STD-M

1.94 0.057

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

XLS/97Teuton

Fax to Dino Vancouver 604-682-3992

14-Oct-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK- 97- 1129

TEUTON RESOURCES CORPORATION
508-875 W. HASTINGS STREET
VANCOUVER, B.C.
V8C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 14
Sample type: CORE
PROJECT: # CLONE
SHIPMENT: # Not Given
Samples submitted by: DALE ROBERTS

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	Li	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	MM-97 17	345	3.6	4.59	<5	115	<5	0.52	2	173	246	888	>10	10	3.56	1278	28	0.02	97	1350	48	<5	<20	12	0.01	<10	287	<10	<1	180
2	MM-97 18	95	3.2	3.75	10	110	<5	0.46	2	199	222	978	>10	10	2.38	812	56	0.02	107	1270	74	<5	<20	8	<0.01	<10	287	10	<1	156
3	MM-97 19	85	3.2	3.84	25	105	<5	1.54	2	157	239	1050	>10	20	2.81	1498	25	0.01	72	1350	40	<5	<20	39	0.01	<10	280	<10	<1	183
4	MM-97 20	100	0.4	4.28	<5	110	<5	3.39	4	31	281	232	>10	10	3.22	1717	19	0.02	42	1680	26	<5	<20	69	0.01	<10	292	<10	<1	199
5	MM-97 21	178	0.4	3.62	<5	105	<5	4.18	<1	21	280	103	9.58	10	2.66	1498	12	0.01	28	1550	18	<5	<20	89	0.01	<10	289	<10	<1	111
6	MM-97 22	20	1.6	3.93	50	110	<5	3.25	1	75	239	231	>10	10	2.83	1531	20	0.01	67	1450	34	<5	<20	55	0.01	<10	270	<10	<1	119
7	MM-97 23	500	1.6	3.37	45	115	<5	4.51	2	35	247	208	>10	10	2.48	1882	17	0.01	58	1480	32	<5	<20	73	0.01	<10	245	<10	<1	116
8	MM-97 24	380	0.2	4.04	<5	125	5	4.24	1	20	255	148	>10	10	3.20	1479	10	0.01	38	1690	22	<5	<20	97	<0.01	<10	284	10	<1	137
9	MM-97 25	>1000	>30	4.84	<5	115	<5	0.48	3	53	65	<1	>10	10	4.19	1007	12	0.01	28	>10000	18	<5	<20	10	<0.01	<10	170	10	<1	270
10	MM-97 26	>1000	>30	1.16	<5	75	<5	0.29	<1	39	88	>10000	9.78	<10	0.65	455	1399	0.02	1	<10	14	<5	<20	18	0.08	<10	58	60	<1	79
11	MM-97 27	75	1.0	2.12	<5	85	<5	0.91	<1	19	74	2012	7.84	<10	0.51	888	21	0.09	2	750	12	<5	<20	38	0.07	<10	50	40	<1	31
12	MM-97 28	10	<0.2	2.81	<5	80	<5	1.80	<1	20	31	144	8.11	10	1.75	1410	18	0.10	1	1230	18	<5	<20	40	0.18	<10	127	20	7	97
13	MM-97 29	20	<0.2	3.27	15	95	<5	2.95	<1	17	60	148	4.80	<10	0.74	904	2	0.16	3	1160	24	<5	<20	50	0.14	<10	76	<10	7	53
14	MM-97 30	15	<0.2	3.00	<5	80	10	2.53	<1	16	37	43	4.58	<10	1.02	1080	1	0.17	<1	1310	24	<5	<20	77	0.15	<10	69	<10	8	82
QC/DATA:																														
Repeat:																														
R/S 1	MM-97 17	335	3.4	4.54	<5	110	<5	0.55	2	175	256	897	>10	10	3.51	1285	24	0.02	94	1480	50	<5	<20	9	0.01	<10	288	<10	<1	187
Repeat:																														
1	MM-97 17	285	3.6	4.51	<5	110	<5	0.53	3	175	248	983	>10	10	3.47	1285	27	0.02	100	1430	50	<5	<20	9	0.01	<10	285	<10	<1	189
Standard:																														
GEO'97		135	1.0	1.83	65	170	<5	1.82	<1	22	65	86	4.37	<10	0.97	713	<1	0.03	22	690	20	5	<20	80	0.12	<10	82	<10	8	72

df/1094
XLS/97Teuton
Fax to Dino Vancouver 604-682-3982

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AK 97- 1130

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

15-Oct-97

ATTENTION: DINO CREMONESE

No. of samples received: 6

Sample type: CORE

PROJECT: # CLONE

SHIPMENT: # Not Given

Samples submitted by: DALE ROBERTS

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)
2	97 DC 51	5.41	0.158	-	-	-
4	97 DC 54	-	-	109.0	3.18	-
5	97 DC 55	31.20	0.910	-	-	-
6	97 DC 56	17.40	0.507	103.0	3.00	5.10

QC/DATA:

Standard:

STD-M	1.94	0.057	-	-	-
MP-1a	-	-	69.7	2.03	1.44
CPb-1	-	-	-	-	0.25

ECO-TECH LABORATORIES LTD

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

XLS/97Teuton

Fax to Dino Vancouver 604-682-3992

9-Oct-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK-97-1130

TEUTON RESOURCES CORPORATION
509-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 6
Sample type: CORE
PROJECT: # CLONE
SHIPMENT: # Not Given
Samples submitted by: DALE ROBERTS

Values in ppm unless otherwise reported

El #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	97 DC 50	500	0.2	3.60	55	90	<5	8.56	1	153	114	547	8.13	10	4.15	1418	3	0.02	37	1430	48	<5	<20	118	0.07	<10	228	<10	<1	43
2	97 DC 51	>1000	<0.2	2.88	30	150	5	1.75	<1	191	14	81	9.47	20	2.74	1317	8	0.02	10	2210	20	<5	<20	27	0.08	<10	182	<10	<1	122
3	97 DC 52	50	1.6	3.95	<5	100	<5	2.15	2	48	12	1901	8.01	20	4.00	2151	4	0.03	11	2450	14	10	<20	34	0.08	<10	182	<10	<1	160
4	97 DC 54	25	>30	1.39	30	200	<5	1.43	2	20	36	8881	2.82	<10	1.34	1364	<1	0.08	12	1490	48	70	<20	25	0.08	<10	110	<10	4	308
5	97 DC 55	>1000	3.6	0.08	30	60	20	0.08	1	15	71	151	>10	10	<0.01	136	34	0.01	<1	210	58	<5	<20	3	<0.01	10	183	<10	<1	37
6	97 DC 56	>1000	>30	4.21	10	105	<5	0.53	3	48	39	>10000	>10	20	3.60	1052	11	0.01	25	>10000	18	<5	<20	10	<0.01	<10	143	<10	<1	228

QC/DATA:

<u>Repeat:</u>																															
R/S 1	97 DC 50	475	0.2	3.54	50	90	<5	8.83	<1	157	120	543	8.07	10	4.09	1419	4	0.02	38	1400	48	5	<20	118	0.07	<10	222	10	<1	42	
<u>Repeat:</u>																															
1	97 DC 50	495	0.2	3.78	50	100	<5	6.89	1	162	120	591	8.57	10	4.34	1493	4	0.02	38	1500	48	<5	<20	123	0.08	<10	240	10	<1	45	
<u>Standard:</u>																															
GEO'97		150	1.4	1.74	85	160	<5	1.86	1	19	68	89	3.88	<10	0.94	674	<1	0.02	22	950	22	<5	<20	54	0.08	<10	76	<10	5	67	

dfl/1088a
XLS/97Teuton
Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

CERTIFICATE OF ASSAY AK 97-1100

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

16-Oct-97

ATTENTION: DINO CREMONESE

No. of samples received: 84

Sample Type: CORE

PROJECT #: CLONE

SHIPMENT #: CL-19

P.O.#: NONE GIVEN

Samples submitted by: DALE ROBERTS

ET #.	Tag #	Au (g/t)	Au (oz/t)	Co (%)
74	62392	5.68	0.166	
75	62393	1.98	0.058	
78	62396			0.031

QC/DATA:

Standard:

STD-M	1.67	0.049	
SU-1a			0.041

XLS/97Teuton
Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

15-Oct-87

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 804-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK-97-1100

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DINO CREMONESE

No. of samples received: 83
Sample Type: core
PROJECT #: Clone
SHIPMENT #: CL-19
Samples submitted by: Dale Roberts

Values in ppm unless otherwise reported

Et#	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	82291	10	1.0	3.07	35	90	<5	4.19	<1	18	36	113	7.42	<10	2.15	1202	5	0.03	3	1710	14	<5	<20	131	0.02	<10	220	<10	<1	74
2	82292	120	1.8	3.28	105	70	<5	5.74	<1	27	28	134	8.14	<10	2.34	1489	8	0.03	6	1680	16	<5	<20	196	0.02	<10	216	<10	<1	80
3	82293	10	1.0	3.33	40	85	<5	3.29	<1	23	35	81	8.59	<10	2.40	1051	7	0.04	2	1880	10	<5	<20	139	0.02	<10	234	<10	<1	90
4	82294	20	1.4	3.64	80	85	<5	3.81	<1	40	34	83	8.05	<10	2.85	1291	8	0.04	4	1900	12	<5	<20	133	0.01	<10	287	<10	<1	114
5	82295	40	0.8	3.87	40	70	5	3.53	<1	29	19	52	8.92	<10	2.67	1247	6	0.04	2	1930	10	<5	<20	128	0.01	<10	284	<10	<1	100
6	82296	20	1.0	4.24	45	55	<5	3.11	<1	24	12	66	9.69	<10	3.31	1348	6	0.04	3	1830	10	<5	<20	117	0.01	<10	298	<10	<1	101
7	82297	5	1.2	3.52	45	60	5	3.88	<1	27	25	63	7.29	<10	3.08	1287	4	0.04	6	1850	10	<5	<20	112	0.02	<10	277	<10	<1	84
8	82305	5	<0.2	3.08	10	185	10	5.75	<1	11	17	2	5.24	<10	2.38	1371	4	0.02	3	1420	4	10	<20	143	<0.01	<10	95	10	<1	102
9	82306	5	<0.2	3.60	<5	320	10	4.91	<1	12	11	2	8.25	<10	2.79	1181	4	0.03	4	1500	4	<5	<20	92	<0.01	<10	117	<10	<1	104
10	82307	60	0.2	3.47	5	185	<5	5.49	<1	20	24	86	6.31	<10	2.38	1184	4	0.04	4	1540	8	<5	<20	111	<0.01	<10	130	<10	<1	108
11	82308	5	<0.2	3.02	<5	740	5	5.88	<1	10	9	2	5.37	<10	2.18	1270	4	0.03	3	1500	4	10	<20	118	<0.01	<10	112	<10	<1	100
12	82309	5	<0.2	2.80	<5	155	10	4.88	<1	10	21	<1	4.94	<10	2.04	1205	3	0.03	2	1430	2	<5	<20	102	<0.01	<10	107	10	<1	85
13	82310	5	<0.2	2.93	20	185	10	8.52	<1	13	27	2	5.77	<10	1.98	1560	3	0.03	4	1350	4	<5	<20	182	<0.01	<10	108	<10	2	98
14	82311	5	<0.2	3.24	10	175	10	5.55	<1	18	14	58	5.95	<10	2.14	1534	5	0.03	2	1580	6	<5	<20	104	<0.01	<10	125	<10	<1	110
15	82312	585	0.8	3.34	10	215	<5	5.36	<1	27	7	318	6.53	<10	2.21	1779	7	0.02	4	1510	6	<5	<20	99	<0.01	<10	133	<10	<1	122
16	82313	5	<0.2	3.34	10	295	10	5.89	<1	12	32	3	5.73	<10	2.44	1527	4	0.02	5	1360	6	<5	<20	144	<0.01	<10	124	<10	<1	115
17	82314	5	<0.2	3.25	<5	430	10	5.28	<1	11	22	4	5.56	<10	2.20	1540	4	0.02	4	1480	4	<5	<20	100	<0.01	<10	106	<10	<1	117
18	82315	10	<0.2	2.83	10	230	10	8.90	<1	11	16	18	5.19	<10	1.56	1782	4	0.01	6	1420	6	<5	<20	158	<0.01	<10	81	<10	4	84
19	82316	330	0.6	3.09	15	170	<5	5.51	<1	19	22	128	5.71	<10	1.65	1239	25	0.01	4	1450	10	<5	<20	138	<0.01	<10	74	<10	<1	73
20	82317	5	<0.2	3.48	<5	450	<5	>10	<1	18	24	51	6.08	<10	2.17	1780	4	0.01	3	1230	4	<5	<20	154	<0.01	<10	99	<10	6	74
21	82318	5	<0.2	3.21	5	1340	10	8.07	<1	8	22	7	5.82	<10	1.83	1884	4	0.01	5	1500	2	<5	<20	186	<0.01	<10	105	<10	<1	88
22	82319	5	<0.2	2.80	5	850	10	5.89	<1	8	33	13	4.92	<10	1.36	1310	4	0.02	4	1440	4	<5	<20	116	<0.01	<10	87	<10	<1	54
23	82320	40	0.6	2.78	10	285	<5	6.48	<1	15	19	189	5.55	<10	1.21	1353	5	0.01	5	1470	4	<5	<20	114	<0.01	<10	82	<10	1	58
24	82321	5	0.2	3.37	10	200	<5	4.36	<1	20	32	47	7.29	<10	1.75	1237	7	0.01	8	1250	4	<5	<20	78	<0.01	<10	95	<10	<1	95
25	82322	15	<0.2	3.93	<5	390	10	3.95	<1	18	70	3	7.83	<10	3.07	1500	4	0.03	17	1590	4	<5	<20	95	0.01	<10	133	<10	<1	187

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1100

ECO-TECH LABORATORIES LTD.

Et#	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	82323	30	<0.2	3.11	<5	180	10	2.97	<1	17	48	8	8.44	<10	2.40	1180	5	0.02	12	870	8	<5	<20	109	<0.01	<10	135	<10	<1	150
27	82324	25	<0.2	2.85	<5	155	10	3.98	<1	16	58	2	5.81	<10	2.37	1318	3	0.01	9	970	6	<5	<20	173	<0.01	<10	123	<10	<1	134
28	82325	10	<0.2	4.09	5	230	10	4.16	<1	23	30	17	8.98	<10	2.70	1650	6	0.02	9	1520	4	<5	<20	114	0.01	<10	170	<10	<1	208
29	82326	5	0.2	2.97	<5	325	<5	3.28	<1	10	29	49	6.26	<10	1.68	1302	4	0.02	9	1700	4	<5	<20	79	0.01	<10	119	<10	<1	151
30	82327	65	2.4	3.09	15	155	<5	5.47	<1	27	93	178	7.75	<10	1.54	2117	8	0.01	24	1280	28	<5	<20	99	<0.01	<10	123	<10	<1	176
31	82328	15	0.8	3.31	15	180	<5	5.74	<1	17	66	95	8.10	<10	1.82	2055	11	0.01	11	1140	12	<5	<20	182	0.01	<10	128	<10	<1	209
32	82329	5	0.2	3.34	5	200	5	6.07	<1	12	32	48	7.50	<10	1.66	2230	5	0.01	5	1380	18	<5	<20	158	0.01	<10	116	<10	<1	187
33	82330	5	0.4	3.50	5	220	<5	3.68	<1	13	24	93	7.76	<10	1.82	1559	5	0.01	8	1620	12	<5	<20	106	<0.01	<10	117	<10	<1	170
34	82331	5	0.4	3.24	20	175	<5	3.06	<1	17	37	98	8.36	<10	2.09	1114	7	0.02	13	1850	8	<5	<20	98	<0.01	<10	114	<10	<1	112
35	82332	5	0.6	3.28	10	310	<5	7.38	<1	9	32	82	5.84	<10	2.28	2083	3	0.02	7	1880	6	<5	<20	208	0.01	<10	111	<10	3	64
36	82333	5	0.6	2.78	15	230	<5	9.25	<1	10	24	75	4.91	<10	1.83	2379	4	0.02	3	1540	8	5	<20	247	<0.01	<10	83	<10	4	59
37	82334	5	1.0	3.03	25	240	<5	8.84	<1	16	31	135	5.36	<10	1.88	1977	7	0.01	7	1840	8	<5	<20	241	<0.01	<10	86	<10	1	82
38	82335	5	1.0	2.88	35	285	<5	8.82	<1	23	34	80	5.57	<10	1.71	1636	5	0.01	8	1740	12	<5	<20	154	<0.01	<10	79	<10	2	122
39	82336	5	1.6	3.17	25	450	<5	8.51	3	23	21	97	5.73	<10	1.90	1626	4	0.01	7	1720	26	<5	<20	134	<0.01	<10	83	<10	1	220
40	82337	5	0.8	4.31	25	485	<5	4.14	<1	24	39	110	7.22	<10	2.89	1182	4	0.01	10	1840	8	<5	<20	105	<0.01	<10	121	<10	<1	185
41	82338	5	0.6	3.37	25	825	<5	8.35	<1	18	17	81	5.30	<10	2.29	1966	4	0.01	4	2080	10	<5	<20	192	<0.01	<10	107	<10	4	111

42	82339	5	0.8	3.96	10	865	<5	5.82	<1	17	38	145	6.18	<10	2.67	1389	5	0.01	10	1780	6	<5	<20	150	<0.01	<10	115	<10	1	125
43	82347	5	1.6	1.89	25	160	<5	7.03	5	17	37	99	3.88	<10	1.12	1323	4	0.01	10	1460	52	10	<20	172	<0.01	<10	58	<10	4	243
44	82348	45	2.4	1.89	75	85	<5	6.57	6	21	31	58	4.52	<10	1.24	1261	8	0.01	17	1260	184	10	<20	148	<0.01	<10	43	<10	2	280
45	82349	70	3.2	1.87	75	110	<5	7.22	14	21	31	106	4.05	<10	1.16	1278	4	0.01	8	1590	242	15	<20	130	<0.01	<10	51	<10	6	652
46	82350	15	2.2	2.32	55	130	<5	7.19	8	20	28	120	4.64	<10	1.51	1158	8	0.02	9	1650	102	<5	<20	218	<0.01	<10	88	<10	2	291
47	82351	15	2.0	2.00	40	130	<5	6.71	8	22	33	70	4.23	<10	1.09	983	4	0.01	8	1510	82	<5	<20	211	<0.01	<10	56	<10	3	350
48	82352	60	2.0	1.72	80	100	<5	8.32	<1	26	33	80	3.98	<10	1.01	1363	5	0.01	7	1290	24	10	<20	287	<0.01	<10	52	<10	4	73
48	82353	90	1.2	2.06	125	105	<5	8.35	<1	20	28	47	4.68	<10	1.23	1183	4	0.01	5	1420	18	5	<20	151	<0.01	<10	58	<10	3	85
50	82354	90	1.8	3.04	85	115	<5	9.15	<1	25	31	108	6.43	<10	2.10	1563	7	0.01	6	1690	28	5	<20	196	<0.01	<10	97	<10	4	143
51	82355	185	3.8	3.84	140	115	<5	5.24	<1	37	20	328	>10	<10	2.59	1302	9	0.01	8	1660	18	<5	<20	134	<0.01	<10	118	<10	<1	161
52	82356	60	2.2	2.00	130	80	<5	7.95	4	26	33	183	8.12	<10	1.82	1533	14	0.01	10	1420	24	10	<20	203	<0.01	<10	80	<10	4	268
53	82357	25	1.4	2.54	80	130	<5	6.96	4	26	21	96	8.31	<10	1.53	1680	5	0.01	7	1750	18	5	<20	219	<0.01	<10	92	<10	<1	268
54	82358	25	0.8	3.31	70	125	<5	7.78	<1	15	31	39	7.36	<10	3.15	1884	5	0.02	6	1540	10	<5	<20	166	<0.01	<10	182	<10	2	60
55	82359	40	0.4	3.12	20	185	10	6.23	<1	11	36	19	6.42	<10	3.06	1253	6	0.03	4	1800	4	<5	<20	185	0.01	<10	199	<10	<1	44
56	82360	185	<0.2	3.30	20	120	10	5.15	<1	13	40	10	6.53	<10	3.25	1159	5	0.03	8	1580	4	<5	<20	128	0.01	<10	221	<10	<1	44
57	82368	35	0.4	3.09	30	160	5	5.20	<1	24	29	50	6.38	<10	2.94	1184	4	0.04	8	1850	6	<5	<20	121	0.05	<10	243	<10	2	56
58	82369	10	<0.2	4.08	15	285	10	3.48	<1	20	43	5	7.87	<10	4.34	1116	4	0.05	9	1780	6	<5	<20	80	0.03	<10	286	<10	<1	85
59	82370	25	1.0	2.27	30	125	<5	6.64	<1	15	31	58	4.31	<10	2.40	1181	2	0.04	4	1040	8	10	<20	197	0.02	<10	145	<10	8	59
60	82371	20	0.4	3.18	15	175	<5	4.98	<1	16	36	68	6.32	<10	3.14	951	4	0.04	7	1480	12	5	<20	118	0.04	<10	231	10	2	86

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1100

ECO-TECH LABORATORIES LTD.

Et.#	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
61	82372	5	<0.2	3.79	5	285	5	4.84	<1	16	37	58	7.55	<10	3.90	1105	2	0.04	9	1590	10	<5	<20	115	0.07	<10	283	<10	2	75
62	82373	5	<0.2	3.83	10	115	5	4.58	<1	16	41	49	7.48	<10	3.88	1140	3	0.03	11	1580	6	<5	<20	111	0.11	<10	270	<10	1	54
63	82374	5	<0.2	3.58	10	80	<5	4.23	1	18	44	31	7.57	<10	3.53	1093	<1	0.04	8	1590	8	<5	<20	118	0.18	<10	284	<10	<1	58
64	82382	5	<0.2	4.09	10	45	10	4.38	<1	18	37	26	8.72	<10	3.83	1025	2	0.05	11	1820	12	<5	<20	130	0.11	<10	292	<10	<1	62
65	82383	5	<0.2	3.60	5	40	5	4.03	<1	17	36	48	8.06	<10	3.28	890	3	0.04	8	1750	14	<5	<20	115	0.05	<10	282	<10	<1	89
66	82384	15	0.2	2.88	25	55	<5	5.88	<1	18	44	189	7.20	<10	2.27	921	4	0.02	12	1620	14	<5	<20	159	0.04	<10	265	<10	<1	70
67	82385	80	2.0	3.11	45	70	<5	4.81	<1	20	32	486	8.44	<10	2.58	780	12	0.02	11	1730	18	<5	<20	144	0.04	<10	292	<10	<1	79
68	82386	40	0.8	3.81	70	80	<5	4.30	<1	21	29	101	9.88	<10	2.92	754	8	0.02	11	2370	20	<5	<20	133	0.03	<10	297	<10	<1	95
69	82387	40	<0.2	3.71	25	75	5	3.53	<1	18	36	49	9.15	<10	3.02	754	8	0.03	8	1780	12	<5	<20	92	0.04	<10	290	<10	<1	81
70	82388	10	<0.2	4.17	20	80	<5	3.01	<1	16	21	62	8.80	<10	3.79	815	5	0.04	11	1980	8	<5	<20	107	0.03	<10	282	<10	<1	76
71	82389	5	<0.2	3.26	<5	240	10	3.84	<1	12	34	14	8.82	<10	3.03	808	3	0.04	8	1810	6	<5	<20	109	0.04	<10	255	<10	<1	54
72	82390	10	<0.2	3.04	20	105	5	4.79	<1	13	38	24	6.34	<10	2.82	879	4	0.05	6	1740	10	<5	<20	139	0.03	<10	240	<10	<1	64
73	82391	75	0.8	2.88	40	55	<5	0.92	4	47	30	174	9.24	<10	2.13	1265	3	0.02	12	1790	18	<5	<20	17	0.17	<10	135	<10	2	988
74	82392	>1000	<0.2	1.73	75	100	<5	0.57	5	103	32	188	7.41	<10	1.19	878	3	0.01	11	1530	24	<5	<20	17	0.16	<10	129	<10	3	1388
75	82393	>1000	0.4	1.45	25	60	<5	0.47	<1	100	23	65	3.97	<10	1.00	833	3	0.02	2	1750	18	<5	<20	10	0.03	<10	69	<10	2	733
76	82394	200	<0.2	2.85	75	70	10	0.70	<1	140	8	83	8.89	<10	2.15	1217	3	0.02	5	1850	22	<5	<20	14	0.18	<10	141	<10	<1	565
77	82395	235	<0.2	2.14	55	165	<5	1.42	<1	177	25	101	8.86	<10	1.79	1187	2	0.01	8	1670	24	<5	<20	32	0.15	<10	138	<10	<1	672
78	82396	575	<0.2	1.72	60	240	<5	1.75	<1	273	30	121	7.24	<10	1.38	980	2	0.01	9	1690	24	<5	<20	33	0.18	<10	121	<10	<1	966
79	82397	40	<0.2	3.05	65	90	10	0.77	<1	168	8	89	>10	<10	2.43	1442	1	0.02	9	1940	20	<5	<20	17	0.21	<10	148	<10	<1	863
80	82398	275	<0.2	2.07	40	80	<5	0.85	<1	144	13	92	6.44	<10	1.65	1002	<1	0.02	5	1790	18	5	<20	19	0.15	<10	103	<10	1	510
81	82399	40	<0.2	1.23	30	155	<5	1.10	<1	48	26	124	3.77	<10	0.87	595	<1	0.01	5	1800	14	5	<20	30	0.10	<10	69	<10	2	279
82	82400	185	0.4	2.55	60	270	<5	2.00	2	139	22	621	8.11	<10	2.29	1378	<1	0.02	11	1830	20	<5	<20	43	0.15	<10	146	<10	<1	283
83	82401	30	<0.2	2.82	20	85	<5	2.88	<1	32	13	190	8.96	<10	2.58	1580	<1	0.03	9	1990	12	<5	<20	43	0.17	<10	168	<10	<1	105
84	82402	60	<0.2	2.92	10	55	<5	3.28	1	41	12	328	9.27	<10	2.67	1570	1	0.03	10	1790	18	<5	<20	50	0.16	<10	191	<10	<1	111

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1100

ECO-TECH LABORATORIES LTD.

El #.	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
QC/DATA:																															
Replit:																															
1	62291	10	1.2	3.07	40	90	<5	4.12	<1	18	31	120	7.28	<10	2.12	1197	6	0.03	3	1740	14	<5	<20	128	0.02	<10	219	10	<1	72	
36	62333	5	0.8	2.78	20	210	<5	9.53	<1	11	27	74	5.05	<10	1.83	2464	6	0.01	4	1810	10	10	<20	245	<0.01	<10	84	20	4	68	
71	62389	5	<0.2	3.26	10	210	5	3.66	<1	13	34	18	6.91	<10	3.01	810	3	0.05	9	1850	8	<5	<20	104	0.04	<10	256	10	<1	56	
Repeat:																															
1	62291	10	1.0	3.08	45	80	<5	4.17	<1	19	34	110	7.41	<10	2.15	1203	5	0.03	3	1760	18	<5	<20	126	0.02	<10	219	<10	<1	75	
10	62307	85	0.2	3.38	10	170	5	5.37	<1	20	20	63	6.18	<10	2.35	1175	4	0.03	4	1500	6	<5	<20	108	<0.01	<10	126	<10	<1	106	
19	62316	315	0.6	3.07	15	180	<5	5.48	<1	18	22	128	5.66	<10	1.64	1235	24	0.01	4	1440	6	<5	<20	138	<0.01	<10	73	<10	<1	73	
36	62333	5	0.8	2.85	25	215	<5	8.96	<1	10	23	73	4.75	<10	1.77	2313	5	0.01	2	1500	8	<5	<20	237	<0.01	<10	80	20	4	58	
45	62349	80	3.0	1.89	70	105	<5	7.37	16	22	32	110	4.15	<10	1.16	1305	4	0.01	9	1820	248	10	<20	133	<0.01	<10	52	<10	6	689	
54	62358	25	0.8	3.36	65	130	10	7.77	<1	15	32	39	7.40	<10	3.21	1690	6	0.02	7	1820	12	<5	<20	165	<0.01	<10	183	<10	2	58	
71	62389	5	<0.2	3.33	10	255	10	3.70	<1	13	35	15	6.96	<10	3.08	822	2	0.05	6	1860	10	<5	<20	109	0.04	<10	256	<10	<1	59	
Standard:																															
GEO'97		130	1.2	1.89	65	155	<5	1.82	<1	19	60	81	4.06	<10	0.98	679	<1	0.03	23	630	18	<5	<20	67	0.13	<10	81	<10	6	66	
GEO'97		135	1.4	1.91	70	150	<5	1.75	<1	19	61	81	4.10	<10	0.97	666	<1	0.03	23	660	20	<5	<20	66	0.13	<10	81	<10	5	68	
GEO'97		125	1.2	1.85	65	150	<5	1.74	<1	19	60	78	4.11	<10	0.95	684	<1	0.03	23	670	22	<5	<20	63	0.13	<10	80	<10	6	71	

dl/1100
 XLS/97Teuton
 Fax to Dino Vancouver 604-882-3992

ECO-TECH LABORATORIES LTD.
 Frank J. Pazzotti, A.Sc.T.
 B.C. Certified Assayer

CERTIFICATE OF ASSAY AK 97 - 1102

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

14-Oct-97

ATTENTION: DINO CREMONESE

No. of samples received: 16

Sample Type: Rock

PROJECT #: Clone

SHIPMENT #: None Given

Samples submitted by: Not Indicated

ET #.	Tag #	Au (g/t)	Au (oz/t)
2	MM-97-02	1.09	0.032
13	MM-97-13	1.00	0.029

XLS/97Teuton

Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

10-Oct-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AK-97-1102

TEUTON RESOURCES CORPORATION
508-875 W. HASTINGS STREET
VANCOUVER, B.C.
V8C 1N2

Phone: 804-573-5700
Fax : 804-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 16
Sample Type: Rock
PROJECT #: Clone
SHIPMENT #: None Given
Samples submitted by: Not Indicated

Values in ppm unless otherwise reported

Et#.	Tag#	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	MM-97-01	170	0.8	1.87	45	65	<5	4.41	<1	29	42	155	6.19	10	1.66	679	7	0.02	27	1290	10	<5	<20	93	<0.01	<10	45	<10	<1	16
2	MM-97-02	>1000	0.8	1.71	15	65	<5	5.53	<1	21	69	199	5.01	<10	1.40	978	7	0.01	51	810	8	<5	<20	97	<0.01	<10	44	<10	<1	12
3	MM-97-03	115	0.6	1.82	<5	60	<5	5.27	<1	19	56	143	4.53	<10	1.22	885	8	0.02	41	1130	6	5	<20	79	<0.01	<10	39	10	<1	11
4	MM-97-04	700	0.8	2.07	15	65	<5	5.45	<1	23	54	211	6.20	10	1.49	1127	6	0.02	14	1450	10	<5	<20	86	<0.01	<10	44	10	<1	17
5	MM-97-05	55	0.2	1.89	<5	70	<5	4.25	<1	17	32	72	4.06	<10	1.24	780	4	0.03	10	1450	6	5	<20	64	<0.01	<10	42	10	<1	11
6	MM-97-06	70	0.8	1.70	15	65	<5	8.53	<1	21	33	80	4.18	<10	1.17	1452	3	0.02	17	1320	6	5	<20	307	<0.01	<10	35	10	1	12
7	MM-97-07	10	1.0	2.42	205	90	<5	6.65	3	18	43	97	4.81	<10	1.92	1351	4	0.03	14	1310	78	10	<20	207	<0.01	<10	92	<10	<1	199
8	MM-97-08	30	1.2	2.78	50	110	<5	8.44	<1	17	45	72	5.07	<10	2.29	1696	4	0.01	18	1410	22	15	<20	254	<0.01	<10	58	<10	<1	50
9	MM-97-09	50	1.8	1.47	55	70	<5	>10	1	12	55	34	3.55	<10	1.34	2292	5	0.01	14	710	18	10	<20	333	<0.01	<10	35	<10	4	59
10	MM-97-10	25	1.0	1.10	65	75	<5	5.00	1	11	97	53	3.24	<10	0.70	950	6	0.01	17	790	12	10	<20	119	<0.01	<10	23	<10	2	94
11	MM-97-11	55	2.2	1.12	130	65	<5	4.38	5	18	78	88	4.52	<10	0.89	1054	13	0.01	45	1150	86	5	<20	145	<0.01	<10	32	<10	5	309
12	MM-97-12	175	2.4	0.21	170	50	<5	0.19	2	5	141	18	2.70	<10	0.03	151	15	<0.01	13	580	148	<5	<20	10	<0.01	<10	11	<10	<1	192
13	MM-97-13	>1000	10.0	0.85	100	70	<5	3.77	1	9	70	30	2.78	<10	0.49	1075	10	0.01	9	620	596	5	<20	118	<0.01	<10	21	<10	3	87
14	MM-97-14	15	0.8	1.86	15	135	<5	8.47	<1	13	34	5	4.74	10	0.56	2731	5	0.01	3	1300	18	<5	<20	191	<0.01	<10	33	<10	7	27
15	MM-97-15	10	0.4	2.15	<5	115	<5	7.27	<1	12	19	4	5.56	20	0.58	2367	5	0.01	1	1480	10	<5	<20	193	<0.01	<10	39	<10	8	32
16	MM-97-16	5	0.4	1.96	<5	215	10	8.35	<1	13	25	4	5.11	20	0.60	2916	5	0.01	2	1450	10	<5	<20	195	<0.01	<10	37	<10	8	31

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1102

ECO-TECH LABORATORIES LTD.

Et#.	Tag#	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
QC/DATA:																															
<i>Repeat:</i>																															
1	MM-97-01	180	0.6	1.92	55	80	<5	4.80	1	32	48	161	6.71	<10	1.72	1041	7	0.02	30	1350	14	<5	<20	91	<0.01	<10	46	<10	<1	16	
<i>Repeat:</i>																															
1	MM-97-01	170	0.6	1.88	50	60	<5	4.82	<1	31	42	155	6.36	<10	1.65	1008	7	0.02	29	1340	14	<5	<20	91	<0.01	<10	45	10	<1	16	
10	MM-97-10	40	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
<i>Standard:</i>																															
ECO97		140	1.2	1.90	70	170	<5	1.84	1	21	63	85	4.29	<10	1.00	719	<1	0.03	24	680	24	<5	<20	64	0.13	<10	83	<10	7	72	

CERTIFICATE OF ASSAY AK 97 - 1103

TEUTON RESOURCES CORPORATION
509-675 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

14-Oct-97

ATTENTION: DINO CREMONESE

No. of samples received: 105

Sample Type: Rock

PROJECT #: Clone

SHIPMENT #: None given

Samples submitted by: Not Indicated

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)
3	V-97-096	2.43	0.071	37.4	1.09	-
4	V-97-097	1.97	0.057	-	-	-
26	V-97-119	-	-	60.4	1.76	-
53	V-97-146	26.10	0.761	-	-	2.12
54	V-97-147	3.24	0.094	-	-	1.17
61	V-97-154	1.09	0.032	-	-	-

QC/DATA:

Standard:

STD-M	1.50	0.044	-	-	-
CPb-1	-	-	-	-	0.25
MP-1a	-	-	69.7	2.03	1.44

ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

XLS/97Teuton

Fax to Dino Vancouver 604-682-3992

14-Oct-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 804-573-5700
Fax : 604-573-4557

ICP CERTIFICATE OF ANALYSIS - AK- 97-1103

TEUTON RESOURCES CORPORATION
508-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

ATTENTION: DRINO CREMONESE

No. of samples received: 105
Sample Type: Rock
PROJECT #: Clone
SHIPMENT #: None Given
Samples submitted by: Not Indicated

Values in ppm unless otherwise reported

Et.#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ce %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	V-97-094	20	1.2	2.08	100	95	<5	3.81	4	20	55	69	5.81	<10	1.32	3791	7	0.01	109	350	6	<5	<20	82	<0.01	<10	48	<10	12	88
2	V-97-095	70	2.0	2.05	285	45	<5	0.49	<1	32	32	83	>10	<10	1.37	646	8	0.01	29	1160	18	<5	<20	8	<0.01	<10	51	<10	<1	23
3	V-97-096	>1000	>30	1.83	2080	50	<5	0.11	<1	25	48	1303	>10	<10	0.91	400	36	<0.01	28	220	2850	<5	<20	<1	<0.01	20	56	<10	<1	623
4	V-97-097	>1000	10.8	1.88	2425	45	<5	0.05	<1	33	42	389	>10	<10	1.14	447	23	<0.01	39	40	120	<5	<20	<1	<0.01	10	44	<10	<1	52
5	V-97-098	85	10.6	1.61	305	100	<5	0.32	<1	35	18	137	9.84	<10	0.70	1373	13	0.01	10	1810	50	<5	<20	6	<0.01	<10	53	<10	<1	177
6	V-97-099	15	<0.2	1.31	<5	205	<5	0.82	<1	18	20	13	4.72	<10	0.67	697	3	0.01	8	1070	10	<5	<20	11	0.03	<10	47	<10	2	132
7	V-97-100	10	<0.2	1.73	5	1235	<5	1.52	<1	11	24	83	4.55	<10	1.18	899	4	0.01	4	980	8	<5	<20	89	0.02	<10	42	<10	2	81
8	V-97-101	5	1.8	2.56	125	100	<5	2.29	<1	26	47	83	5.30	<10	1.66	875	5	0.01	13	1350	54	<5	<20	35	<0.01	<10	62	<10	<1	77
9	V-97-102	5	1.4	3.63	190	160	<5	0.82	<1	24	52	70	7.08	<10	2.89	749	8	0.02	18	1280	34	<5	<20	15	<0.01	<10	134	<10	<1	84
10	V-97-103	650	10.6	1.39	305	60	<5	7.55	62	16	46	109	4.61	<10	0.69	2239	5	0.01	5	930	1448	15	<20	153	<0.01	<10	36	<10	<1	3828
11	V-97-104	5	1.4	1.35	20	1070	<5	4.81	8	8	39	35	5.78	<10	0.72	2285	5	0.01	2	910	100	<5	<20	81	0.03	<10	49	<10	<1	381
12	V-97-105	5	1.0	2.36	<5	780	<5	6.39	1	15	21	53	4.32	<10	1.34	1622	4	0.02	3	1180	40	<5	<20	100	<0.01	<10	50	<10	1	212
13	V-97-106	5	0.4	1.83	20	830	<5	3.57	5	20	29	33	4.72	<10	0.90	1308	4	0.02	4	1180	50	10	<20	48	0.02	<10	55	<10	<1	424
14	V-97-107	5	<0.2	1.02	5	220	<5	1.83	1	15	42	10	4.82	<10	0.47	697	5	0.02	<1	1470	16	<5	<20	36	0.02	<10	69	<10	3	79
15	V-97-108	5	<0.2	1.51	<5	305	5	1.55	<1	16	28	8	5.61	<10	1.09	591	4	0.02	4	1240	12	<5	<20	26	0.03	<10	57	<10	2	64
16	V-97-109	5	<0.2	1.50	10	110	<5	3.43	<1	14	23	8	3.31	<10	1.30	1078	3	0.02	5	940	8	5	<20	80	0.02	<10	27	<10	3	57
17	V-97-110	5	<0.2	1.49	<5	215	5	1.79	<1	15	22	7	4.74	<10	1.40	618	3	0.02	6	850	10	<5	<20	34	0.02	<10	54	<10	<1	63
18	V-97-111	5	<0.2	1.02	10	120	10	0.30	<1	14	22	7	5.00	<10	0.74	296	4	0.02	3	480	10	<5	<20	8	0.03	<10	48	<10	<1	58
19	V-97-112	5	<0.2	1.00	<5	125	5	2.27	<1	17	24	8	4.62	<10	0.80	638	3	0.02	3	620	14	<5	<20	53	0.02	<10	49	<10	<1	77
20	V-97-113	5	1.8	3.58	65	235	<5	3.08	1	23	28	88	8.93	<10	2.12	1934	5	0.02	8	1550	46	<5	<20	55	<0.01	<10	95	<10	2	203
21	V-97-114	15	0.2	2.08	10	75	<5	9.85	<1	18	26	102	3.72	<10	1.28	1543	3	0.01	3	1930	10	10	<20	232	<0.01	<10	49	<10	6	47
22	V-97-115	15	0.6	1.69	55	115	<5	5.96	<1	12	44	31	4.47	<10	0.65	1253	6	0.01	6	970	8	<5	<20	201	<0.01	<10	31	<10	2	72
23	V-97-116	135	18.0	0.37	240	35	<5	2.29	4	13	117	97	4.32	<10	0.38	875	14	0.01	27	800	200	5	<20	58	<0.01	<10	15	<10	3	432
24	V-97-117	85	2.6	0.70	215	50	<5	1.01	7	14	92	42	4.48	<10	0.48	822	11	0.01	22	850	234	<5	<20	29	<0.01	<10	22	<10	1	633
25	V-97-118	35	2.4	0.87	105	65	<5	2.95	9	20	68	134	4.23	<10	1.07	1352	8	0.01	32	1040	112	<5	<20	110	<0.01	<10	25	<10	6	619

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK- 97-1103

ECO-TECH LABORATORIES LTD.

Et.#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ce %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	V-97-119	890	>30	0.52	500	30	<5	0.60	1	19	94	305	7.05	<10	0.28	837	14	0.01	23	800	3822	15	<20	15	<0.01	<10	17	<10	<1	857
27	V-97-120	335	2.6	1.88	95	70	<5	2.14	<1	17	88	334	4.44	<10	1.87	558	8	0.01	12	1120	48	<5	<20	77	<0.01	<10	53	<10	<1	102
28	V-97-121	150	1.8	1.36	75	65	<5	3.83	1	15	71	78	4.02	<10	1.32	907	8	0.01	32	1040	22	<5	<20	113	<0.01	<10	34	<10	3	194
29	V-97-122	55	1.8	1.45	75	60	<5	2.73	1	16	80	75	3.76	<10	1.17	598	9	0.01	33	1000	18	5	<20	96	<0.01	<10	36	<10	1	159
30	V-97-123	20	1.6	1.38	80	50	<5	1.96	<1	16	97	72	4.09	<10	1.08	452	8	0.01	34	1010	20	<5	<20	68	<0.01	<10	36	<10	<1	151
31	V-97-124	15	1.0	2.45	115	85	<5	8.32	<1	21	51	101	4.99	<10	2.19	1714	5	0.02	23	1330	12	<5	<20	245	<0.01	<10	66	<10	2	117
32	V-97-125	40	0.8	2.23	135	85	<5	6.12	<1	19	37	115	4.42	<10	1.79	1405	5	0.02	23	1320	10	<5	<20	159	<0.01	<10	72	<10	<1	37
33	V-97-126	35	0.4	1.40	70	60	<5	6.01	<1	17	88	124	3.91	<10	0.86	1410	7	0.01	40	740	12	5	<20	141	<0.01	<10	34	<10	2	22
34	V-97-127	15	0.4	1.44	110	125	<5	5.59	<1	15	40	71	3.96	<10	1.42	1141	3	0.01	11	1370	4	<5	<20	105	<0.01	<10	32	<10	2	13
35	V-97-128	10	0.6	1.18	70	95	<5	5.48	<1	17	36	85	3.11	<10	0.92	995	2	0.01	11	1420	4	<5	<20	83	<0.01	<10	28	<10	2	12
36	V-97-129	35	1.4	0.97	95	50	<5	9.15	<1	23	73	171	4.78	<10	1.06	1701	9	0.01	52	370	10	<5	<20	149	<0.01	<10	50	<10	3	16
37	V-97-130	40	1.6	1.37	45	100	<5	9.90	2	11	66	68	3.52	<10	1.28	2051	5	0.01	13	720	8	<5	<20	161	<0.01	<10	45	<10	3	388
38	V-97-131	55	0.8	1.77	50	75	<5	5.28	2	13	39	58	4.11	<10	1.37	1250	5	0.01	26	770	8	10	<20	70	<0.01	<10	31	<10	1	336
39	V-97-132	40	1.0	2.08	20	150	<5	9.40	<1	25	47	257	5.09	<10	1.78	1747	8	0.01	19	1820	8	<5	<20	187	<0.01	<10	54	<10	2	110
40	V-97-133	15	1.0	2.02	20	160	<5	8.16	<1	22	56	211	5.04	<10	1.62	1596	7	0.01	18	1890	8	<5	<20	191	<0.01	<10	56	<10	2	100

41	V-97-134	20	1.6	2.09	20	200	<5	9.33	<1	21	54	255	4.99	<10	1.81	1750	7	0.01	15	1860	8	<5	<20	172	<0.01	<10	58	<10	2	163
42	V-97-135	10	0.8	2.36	20	95	<5	8.84	<1	23	54	303	5.37	<10	2.10	1675	8	0.01	23	1730	6	<5	<20	236	<0.01	<10	66	<10	2	44
43	V-97-136	15	0.2	1.74	10	155	<5	6.71	<1	17	63	119	3.74	<10	1.35	1392	5	0.02	12	1200	4	5	<20	185	<0.01	<10	43	<10	2	20
44	V-97-137	5	<0.2	0.81	5	130	<5	2.78	<1	4	77	6	1.83	<10	0.33	817	4	0.02	<1	440	4	<5	<20	111	<0.01	<10	9	<10	2	11
45	V-97-138	5	<0.2	0.68	10	270	<5	3.74	<1	2	59	20	1.35	10	0.25	1067	3	0.01	<1	430	4	<5	<20	144	<0.01	<10	5	<10	3	16
46	V-97-139	5	<0.2	0.60	<5	215	<5	2.87	<1	4	34	4	1.75	<10	0.33	757	4	0.01	<1	430	4	<5	<20	108	<0.01	<10	6	<10	2	15
47	V-97-140	5	<0.2	1.45	<5	480	<5	2.38	<1	3	66	4	3.00	<10	0.80	662	5	0.02	<1	410	6	<5	<20	46	<0.01	<10	12	<10	<1	21
48	V-97-141	15	0.4	2.51	25	185	<5	6.98	<1	22	68	114	5.40	<10	1.61	1577	5	0.01	20	1470	8	<5	<20	153	<0.01	<10	67	<10	<1	29
49	V-97-142	10	0.4	1.90	20	95	<5	>10	<1	29	83	102	5.56	<10	1.78	1791	5	0.01	26	1700	8	<5	<20	217	<0.01	<10	86	<10	3	23
50	V-97-143	5	0.6	1.97	15	110	<5	9.89	<1	29	55	187	6.36	<10	2.34	1848	5	0.01	24	1550	6	<5	<20	228	<0.01	<10	71	<10	1	44
51	V-97-144	25	<0.2	2.40	10	255	<5	>10	<1	20	75	79	5.29	<10	2.23	1843	5	0.01	24	1420	4	5	<20	239	<0.01	<10	81	<10	2	17
52	V-97-145	25	<0.2	2.13	10	70	<5	8.90	<1	24	74	99	4.90	<10	1.87	1689	5	0.01	19	1220	4	<5	<20	183	<0.01	<10	89	10	1	17
53	V-97-146	>1000	25.6	0.33	10	45	<5	>10	<1	11	43	>10000	2.40	30	0.19	3172	8	0.01	4	<10	8	<5	<20	256	0.01	<10	10	10	46	34
54	V-97-147	>1000	14.6	2.05	20	65	<5	9.93	<1	29	85	>10000	5.80	<10	1.39	2160	7	0.02	22	1270	8	<5	<20	201	0.01	<10	99	<10	3	61
55	V-97-148	25	0.8	2.92	20	90	<5	7.78	<1	22	58	906	6.04	<10	2.31	1688	8	0.02	19	1540	8	<5	<20	239	<0.01	<10	112	<10	<1	50
56	V-97-149	65	0.8	2.36	30	60	<5	5.74	<1	24	78	750	5.08	<10	2.01	1107	7	0.02	14	1680	6	<5	<20	137	<0.01	<10	94	<10	<1	30
57	V-97-150	35	0.4	2.33	15	65	<5	5.61	<1	21	94	308	4.64	<10	1.89	983	6	0.02	12	1610	6	<5	<20	118	<0.01	<10	87	<10	<1	25
58	V-97-151	10	<0.2	1.54	<5	160	<5	5.11	<1	10	49	34	3.19	<10	0.98	1136	4	0.01	8	750	8	<5	<20	152	<0.01	<10	24	<10	<1	12
59	V-97-152	25	0.2	2.65	20	85	<5	>10	<1	26	71	125	5.77	<10	2.54	1925	4	0.01	29	1580	4	<5	<20	272	<0.01	<10	87	<10	1	23
60	V-97-153	820	1.4	2.42	10	50	<5	6.29	<1	30	83	960	5.82	<10	1.58	1539	7	0.01	22	1280	8	<5	<20	158	<0.01	<10	87	<10	<1	38

TETON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1103

ECO-TECH LABORATORIES LTD.

Et#	Tag #	Au(ppb)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
61	V-97-154	>1000	5.0	2.56	20	45	<5	6.52	2	27	89	3420	5.51	<10	2.28	1318	8	0.02	19	1350	4	<5	<20	272	<0.01	<10	140	<10	<1	110
62	V-97-155	50	0.8	2.30	30	80	<5	4.56	<1	21	52	314	5.08	<10	2.01	920	8	0.02	12	1680	8	<5	<20	117	<0.01	<10	102	<10	<1	42
63	V-97-156	40	0.4	3.03	<5	85	<5	7.84	<1	23	118	245	6.11	<10	3.01	1201	8	0.02	30	1750	2	<5	<20	220	<0.01	<10	189	<10	<1	41
64	V-97-157	5	<0.2	2.68	<5	200	5	4.49	<1	15	30	11	7.48	<10	0.95	1206	5	0.01	1	1010	2	<5	<20	70	<0.01	<10	55	<10	<1	63
65	V-97-158	5	<0.2	1.43	<5	200	<5	2.78	<1	8	33	20	2.97	<10	0.53	1047	4	0.01	<1	1180	4	<5	<20	65	<0.01	<10	20	<10	2	38
66	V-97-159	10	0.4	2.19	20	125	<5	2.07	<1	16	30	74	5.00	<10	1.37	1438	6	0.01	32	880	12	<5	<20	37	<0.01	<10	37	<10	<1	77
67	V-97-160	20	0.6	1.81	75	150	<5	0.96	<1	22	32	57	4.84	<10	0.83	876	7	0.01	38	1250	18	<5	<20	39	<0.01	<10	52	<10	1	82
68	V-97-161	55	1.0	1.73	<5	1735	<5	3.36	1	10	56	57	4.97	<10	1.16	1185	3	0.02	11	1200	26	<5	<20	156	0.02	<10	96	<10	<1	175
69	V-97-162	15	1.0	0.79	<5	215	<5	3.81	1	9	38	82	3.68	<10	0.32	1650	3	0.01	<1	1090	30	<5	<20	57	0.03	<10	71	<10	4	78
70	V-97-163	10	0.6	0.39	10	1140	<5	>10	1	<1	30	9	2.11	<10	0.09	2918	2	0.01	<1	790	18	5	<20	210	0.02	<10	22	<10	8	18
71	V-97-164	10	0.4	2.08	15	125	<5	2.09	1	21	29	64	4.82	<10	1.11	1059	5	0.01	4	1360	18	<5	<20	39	<0.01	<10	47	<10	<1	203
72	V-97-165	10	4.4	1.65	60	285	<5	0.26	6	22	28	91	6.12	<10	0.89	1830	8	0.01	4	1200	166	<5	<20	7	<0.01	<10	30	<10	5	422
73	V-97-166	10	1.0	2.49	20	305	<5	3.79	<1	14	22	81	5.35	<10	1.24	1688	4	0.01	5	1630	44	<5	<20	50	<0.01	<10	62	<10	<1	111
74	V-97-167	15	0.8	2.58	20	310	5	1.13	<1	18	21	14	6.11	<10	1.39	1147	4	0.01	<1	1780	10	<5	<20	13	<0.01	<10	46	<10	3	120
75	V-97-168	5	<0.2	1.20	<5	785	10	1.77	<1	11	24	4	4.28	<10	0.83	952	2	0.01	7	830	10	<5	<20	41	0.03	<10	37	<10	2	49
76	V-97-169	85	12.2	4.42	160	110	<5	1.98	4	34	118	122	>10	<10	1.78	3038	12	0.01	48	1190	12	<5	<20	45	0.01	<10	138	<10	<1	508
77	V-97-170	5	0.4	2.58	25	70	<5	3.37	<1	16	30	9	7.43	<10	0.85	2378	7	0.01	<1	1280	8	<5	<20	52	<0.01	<10	48	<10	<1	32
78	V-97-171	30	0.2	3.05	10	215	<5	4.45	<1	13	19	216	6.45	<10	2.04	1358	3	0.02	5	1230	14	<5	<20	85	<0.01	<10	107	<10	<1	108
79	V-97-172	5	<0.2	1.27	<5	1985	<5	4.55	<1	4	21	5	4.05	<10	0.78	2225	2	0.01	2	560	6	5	<20	197	0.03	<10	31	10	3	30
80	V-97-173	10	0.8	2.79	20	175	<5	0.68	26	19	27	51	5.74	<10	1.74	578	3	0.01	12	1030	12	<5	<20	10	<0.01	<10	68	<10	<1	2478
81	V-97-174	15	1.8	2.97	45	90	<5	1.02	1	18	39	145	6.48	<10	2.05	804	6	0.01	10	1760	14	<5	<20	11	<0.01	<10	86	<10	<1	267
82	V-97-175	5	<0.2	2.32	20	115	<5	6.64	<1	21	53	19	5.13	<10	1.83	1780	4	0.01	19	1700	8	<5	<20	114	0.01	<10	80	<10	2	31
83	V-97-176	45	1.4	2.08	20	105	<5	9.41	<1	30	81	1045	4.03	<10	1.97	1939	6	0.01	24	1520	6	10	<20	268	<0.01	<10	73	10	3	17
84	V-97-177	10	<0.2	4.08	<5	55	<5	6.51	<1	37	197	119	6.89	<10	5.37	1088	<1	0.02	40	1720	8	<5	<20	228	0.23	<10	255	<10	2	48
85	V-97-178	5	0.2	1.81	60	95	<5	>10	<1	20	44	34	5.05	<10	1.88	1911	3	0.01	25	1630	8	<5	<20	280	<0.01	<10	83	10	4	14
86	V-97-179	20	2.0	1.21	65	55	<5	0.17	<1	5	182	90	3.59	<10	0.72	302	28	<0.01	59	360	154	<5	<20	4	<0.01	<10	125	<10	<1	27
87	V-97-180	25	1.2	1.03	65	75	<5	1.62	3	13	89	183	3.36	<10	0.59	759	5													

94	V-97-187	5	2.4	0.82	5	305	<5	0.73	<1	5	64	38	3.06	<10	0.08	708	3	0.01	<1	1020	22	<5	<20	17	0.04	<10	44	<10	3	65
95	V-97-188	5	<0.2	0.50	<5	305	<5	2.78	<1	4	62	5	2.85	<10	0.08	1690	4	0.01	<1	950	14	<5	<20	50	0.02	<10	43	<10	3	16

TEUTON RESOURCES CORPORATION

ICP CERTIFICATE OF ANALYSIS - AK-97-1103

ECO-TECH LABORATORIES LTD.

Et.#	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
96	V-97-189	15	2.0	1.91	185	95	<5	4.41	<1	14	27	100	4.11	<10	1.29	1188	5	0.02	<1	920	74	<5	<20	87	<0.01	<10	53	<10	<1	52
97	V-97-190	25	0.6	3.81	45	145	10	3.57	1	24	19	58	8.36	<10	2.04	2002	10	0.01	8	1050	40	<5	<20	110	<0.01	<10	122	<10	<1	308
98	V-97-191	10	4.0	2.64	100	85	<5	6.88	60	24	30	154	5.26	<10	1.91	2049	5	0.02	9	1210	620	10	<20	124	<0.01	<10	68	<10	<1	2498
99	V-97-192	5	<0.2	1.87	10	230	<5	0.73	<1	13	21	6	4.38	<10	1.15	679	4	0.01	3	800	14	<5	<20	16	0.01	<10	33	<10	2	72
100	V-97-193	5	<0.2	2.42	<5	160	<5	5.53	<1	15	9	5	5.28	<10	0.93	1508	4	0.01	3	670	6	<5	<20	87	<0.01	<10	28	<10	3	44
101	V-97-195-A	555	0.6	3.73	<5	130	<5	2.14	<1	21	37	98	7.10	<10	2.60	1490	5	0.02	8	1370	26	<5	<20	59	<0.01	<10	139	<10	<1	174
102	V-97-195-B	10	<0.2	4.67	5	300	5	3.16	2	34	21	40	>10	<10	2.81	2027	7	0.02	20	1250	28	<5	<20	75	<0.01	<10	171	<10	<1	375
103	V-97-196	135	5.6	2.44	235	155	<5	0.42	<1	27	37	437	7.75	<10	1.49	719	7	0.01	6	1110	28	<5	<20	7	<0.01	<10	73	<10	<1	89
104	V-97-197	35	2.0	1.90	55	200	<5	0.83	<1	11	30	229	4.02	<10	1.12	572	3	0.01	8	1470	12	<5	<20	13	<0.01	<10	48	<10	<1	87
105	V-97-198	10	1.8	0.86	75	235	<5	1.07	4	10	47	78	2.31	<10	0.29	681	4	0.01	18	990	8	<5	<20	11	<0.01	<10	15	<10	4	481

QC DATA:

Repeat:

1	V-97-094	20	1.2	2.08	105	90	<5	3.50	3	20	59	84	5.78	<10	1.29	3688	7	0.01	107	390	10	<5	<20	60	<0.01	<10	48	10	12	86
38	V-97-129	40	1.8	0.97	90	50	<5	8.88	<1	22	78	173	4.63	<10	1.08	1889	8	0.01	48	390	12	<5	<20	144	<0.01	<10	49	10	3	15
71	V-97-164	10	0.4	2.14	25	140	<5	2.20	1	21	34	84	4.92	<10	1.13	1085	4	0.01	4	1420	20	<5	<20	39	<0.01	<10	48	<10	<1	203

Repeat:

1	V-97-094	25	1.2	2.14	110	95	<5	3.65	3	20	57	71	5.87	<10	1.35	3829	7	0.01	108	390	8	<5	<20	82	<0.01	<10	49	<10	13	89
10	V-97-103	635	11.2	1.42	310	60	<5	7.70	63	18	47	107	4.66	<10	0.70	2264	5	0.01	5	950	1468	15	<20	155	<0.01	<10	37	<10	<1	3880
19	V-97-112	5	<0.2	1.03	<5	125	<5	2.25	<1	17	24	8	4.76	<10	0.80	636	3	0.02	3	620	12	<5	<20	52	0.03	<10	52	<10	<1	67
38	V-97-129	35	1.8	0.97	95	50	<5	9.03	<1	23	77	170	4.78	<10	1.05	1696	9	0.01	52	400	12	<5	<20	142	<0.01	<10	49	<10	3	16
45	V-97-138	5	<0.2	0.69	<5	270	<5	3.89	<1	2	57	25	1.33	10	0.25	1090	3	0.01	<1	410	4	<5	<20	145	<0.01	<10	5	<10	3	17
54	V-97-147	>1000	15.8	2.09	25	85	<5	>10	<1	30	87	>10000	6.08	<10	1.41	2198	7	0.02	23	1220	8	<5	<20	207	0.01	<10	101	10	4	57
71	V-97-164	10	0.2	2.17	20	135	<5	2.15	2	21	30	65	5.02	<10	1.14	1085	5	0.01	5	1440	16	<5	<20	38	<0.01	<10	49	<10	<1	208
80	V-97-173	10	0.6	2.80	15	195	<5	0.88	26	20	26	50	5.73	<10	1.73	575	3	0.01	13	1020	10	<5	<20	11	<0.01	<10	89	<10	<1	2492
89	V-97-182	5	0.2	1.49	20	215	<5	5.50	<1	10	58	11	3.84	<10	0.46	1767	5	0.01	1	710	12	<5	<20	122	<0.01	<10	25	<10	2	10

Standard:

GEO'97		140	1.2	1.81	70	150	<5	1.75	<1	19	60	83	4.12	<10	0.97	697	<1	0.03	23	650	24	<5	<20	82	0.12	<10	79	<10	5	73
GEO'97		130	1.0	1.75	85	145	<5	1.89	<1	19	64	79	3.89	<10	0.94	696	<1	0.03	24	640	18	<5	<20	80	0.12	<10	77	<10	6	67
GEO'97		125	1.0	1.76	70	145	<5	1.84	<1	18	62	78	3.98	<10	0.94	658	<1	0.03	24	640	20	<5	<20	80	0.12	<10	77	<10	7	68

d/1095
XLS/97Teuton
Fax to Dino Vancouver 604-882-3992

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

9-Oct-87

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS - AK-87-1104

TEUTON RESOURCES CORPORATION
500-875 W. HASTINGS STREET
VANCOUVER, B.C.
V6C 1N2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: DINO CREMONESE

No. of samples received: 8
Sample Type: Rock
PROJECT #: Clone
SHIPMENT #: None Given
Samples submitted by: Not Indicated

Values in ppm unless otherwise reported

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	V-97-07	30	2.0	0.58	75	85	<5	0.18	1	13	88	58	3.20	<10	0.21	415	7	<0.01	10	580	10	<5	<20	7	<0.01	<10	9	<10	2	93
2	V-97-08	115	2.2	0.88	70	70	10	0.19	<1	15	82	70	4.10	<10	0.42	470	8	<0.01	10	730	18	<5	<20	7	<0.01	<10	16	10	<1	93
3	V-97-09	55	2.0	0.61	95	100	<5	0.17	3	9	84	43	2.51	<10	0.32	814	7	<0.01	17	580	18	<5	<20	8	<0.01	<10	13	<10	<1	193
4	V-97-10	75	2.2	0.86	530	90	<5	0.19	4	18	82	128	4.80	<10	0.36	913	14	<0.01	40	740	26	<5	<20	8	<0.01	<10	32	<10	3	354
5	V-97-11	495	10.4	0.65	3755	70	<5	0.21	5	18	68	424	4.43	<10	0.41	828	9	<0.01	11	530	34	30	<20	7	<0.01	<10	14	<10	<1	483
6	V-97-12	895	23.2	0.33	2075	70	<5	0.14	<1	11	88	253	4.28	<10	0.10	427	8	0.01	3	410	50	<5	<20	3	<0.01	<10	5	<10	<1	195
7	V-97-13	140	1.2	1.84	75	105	5	0.59	2	18	27	58	8.01	10	0.93	1252	8	0.02	3	1590	12	<5	<20	13	<0.01	<10	46	<10	4	175
8	V-97-14	15	<0.2	2.81	10	55	<5	2.02	<1	27	81	802	5.08	<10	2.64	624	4	0.03	21	1770	10	5	<20	38	0.07	<10	147	10	2	27

QC/DATA:

Repeat:

1	V-97-07	30	2.0	0.54	80	75	<5	0.17	<1	12	66	53	2.97	<10	0.21	378	6	<0.01	8	580	8	<5	<20	6	<0.01	<10	9	<10	2	87
---	---------	----	-----	------	----	----	----	------	----	----	----	----	------	-----	------	-----	---	-------	---	-----	---	----	-----	---	-------	-----	---	-----	---	----

Repeat:

1	V-97-07	30	2.0	0.58	70	75	<5	0.18	2	13	86	58	3.18	<10	0.23	407	8	<0.01	9	580	10	<5	<20	6	<0.01	<10	10	<10	2	82
---	---------	----	-----	------	----	----	----	------	---	----	----	----	------	-----	------	-----	---	-------	---	-----	----	----	-----	---	-------	-----	----	-----	---	----

Standard:

GEO'97	130	1.0	1.82	80	155	<5	1.88	<1	18	80	81	3.89	<10	0.98	654	<1	0.02	20	830	20	<5	<20	60	0.08	<10	78	<10	5	88
--------	-----	-----	------	----	-----	----	------	----	----	----	----	------	-----	------	-----	----	------	----	-----	----	----	-----	----	------	-----	----	-----	---	----

dlr1089
XLS/97Teuton
Fax to Dino Vancouver 604-682-3992

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

APPENDIX II

Drill Hole Logs DDH-97-127-143

TEUTON RESOURCES CORPORATION LTD

PROPERTY: Clone Property				HOLE No. DDH-CI-97-127							
Azimuth: 160 degree		Dip: -45 degree		Depth: 114.3 m		Date:		Logged by: ERK			
Meterage From To	Rock Type	Alteration, Mineralization & Structure Description	Sample No.	Sample Interval		Assay / Geochem					
				From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)	
1.52	5.85	Homblende Feldspar Breccia	Strong hematite alteration, limonite plus local minor malachite on fractures.	59751	2	3.5	1.5	>1000	40	46	15
			Fine grained, red, mottled, fragmental, foliated with strong hematite stockwork	59752	3.5	5	1.5	130	28	29	5
			Fractures @ 45 deg, foliation @ 45 deg	59753	5	6.5	1.5	115	66	472	130
			Frs= 7/m Vns=25/m	59754	6.5	8	1.5	555	257	607	315
			Weak patchy silica	59755	8	9.5	1.5	15	97	762	115
			Strong pervasive chlorite	59756	9.5	11	1.5	10	52	61	30
			Moderate pervasive carbonate	59757	11	12.5	1.5	5	23	115	30
			Strong pervasive k-spar	59758	12.5	14	1.5	10	13	92	45
			Strong hematite stockwork	59759	14	15.5	1.5	15	13	83	40
			Moderate bleb pyrite	59760	15.5	17	1.5	5	14	87	40
			Weak quartz microveins	59761	17	18.5	1.5	240	31	114	40
				59762	18.5	20	1.5	25	19	81	30
			3.05 - 3.5 m, Coarse pyrite blebs with intense chlorite and k-spar alteration	59763	20	21.5	1.5	25	44	15	60
				59764	21.5	23	1.5	0.054	77	123	90
5.85	11.95	Homblende feldspar breccia	Generally weak quartz/calcite stockwork, minor hematite as blebs and veinlets	59765	23	24.5	1.5	5	17	204	45
			Mottling due to dark chlorite - numerous chlorite veinlets up to 5 mm wide	59766	24.5	26	1.5	110	14	85	60
			Fine grained, green. Foliated, veined, mottled. Foliation 45 deg, fractures	59767	26	27	1	10	50	78	100
			30 deg	59768	27	28	1	0.052	120	98	565
			Frs = 6/m Vns = 10/m	59769	28	29	1	5	15	76	85
			Trace Si patches	59770	29	30	1	5	31	130	90
			Strong pervasive chlorite	59771	30	31	1	5	61	68	100
			Moderate pervasive carbonate	59772	31	32	1	6	51	116	110
			Moderate pervasive k-spar	59773	32	33	1	5	46	123	120
			Weak hematite stockwork	59774	33	34	1	5	70	102	155
			Weak disseminated pyrite	59775	34	35	1	5	16	47	215
			Weak quartz microveins	59776	35	36	1	5	13	26	56
				59777	36	37	1	10	153	140	235
			5.85 - 6.9m Strong k-spar alteration. Minor 1 cm wide pyrite veinlets at 6 m.	59778	37	37.8	0.8	475	284	276	1045
	59779	37.8	39	1.2	0.083	501	351	6380			
11.95	18.2	Homblende Feldspar Crystalline	Weak qtz/calcite stockwork, locally vuggy where calcite has weathered out.	59780	39	40	1	0.179	548	1546	1510
			Fine grained, red, Crystalline.	59781	40	41	1	205	137	360	285
			Fractures 30 deg, veins 45 deg. Frs =7/m vns = 3/m	59782	41	42	1	5	65	125	120
			Weak patchy silica alteration	59783	42	43	1	30	67	138	110
			Weak pervasive chlorite	59784	43	44	1	0.188	444	172	625
			Weak pervasive carbonate	59785	44	45	1	210	447	153	615
			Weak pervasive k-spar	59786	45	46	1	205	275	74	335
			Weak disseminated pyrite	59787	46	47	1	305	43	331	50
			Weak quartz microveins	59788	47	48	1	180	36	588	60
				59789	48	49	1	205	43	479	100
			Strong qtz/calcite stockwork, minor chlorite veinlets up to 2 mm, minor hematite veins approx. 2-3 mm. Local strong K-spar alteration.	59790	49	50	1	0.411	1362	1231	1.13
			Medium grained, red. Mottled, veined with stockwork. Fracture 45 deg, veins 45 deg. Frs = 8/m vns = 10/m	59791	50	51	1	0.066	94	697	455
				59792	51	52	1	555	57	1759	165
				59793	52	53	1	115	33	172	145
Weak patchy silica	59794	53	54	1	125	41	207	95			
Strong pervasive chlorite	59795	54	55	1	55	46	480	80			
Moderate pervasive carbonate	59796	55	56	1	15	62	154	85			
Strong pervasive k-spar	59797	56	57	1	60	45	409	50			
Strong hematite stockwork	59798	57	58	1	105	33	324	90			
Weak disseminated pyrite	59799	58	59	1	50	24	205	55			
Weak qtz microveins	59800	59	60	1	15	34	203	35			
	59801	60	60.96	0.96	50	18	46	15			
23.1	42.8	Homblende feldspar Breccia	Mottled light to dark green depending on chlorite. @ 27.05 to 27.25 - arsenopyrite stringers with intense k-spar alteration and chlorite.	61822	61	62	1	15	28	15	30
				61823	62	63	1	15	24	15	20
			Medium grained, green. Fractures 45 deg veins 45 deg Frs =6/m vns =4/m	61824	63	64	1	0.048	41	0.048	130
			Weak patchy silica	61825	64	65	1	455	35	455	75
			Moderate pervasive chlorite	61826	65	66	1	0.16	66	0.16	205

TEUTON RESOURCES CORPORATION LTD

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample No.	Sample Interval		Assay / Geochem				
From	To				From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
			Moderate pervasive carbonate	61827	66	67	1	215	13	215	20
			Moderate pervasive k-spar	61828	67	68	1	0.033	9	0.033	25
			Moderate bleb pyrite	61829	68	68.95	1	380	14	380	100
			Quartz microveins	61830	69	70	1	45	22	45	395
				61831	70	71	1	130	15	89	15
			27 to 39.7 m - Local fine arsenopyrite xls < 1 %	61832	71	72	1	240	17	140	10
			37.8 to 39 m - Minor arsenopyrite stringers along fractures approx. 3-4 %	61833	72	73	1	80	13	135	5
			39 to 39.57 m - Coarse bleb pyrite along hematite filled fractures. Pyrite approximately 10%.	61834	73	74	1	230	14	94	5
				61835	74	75	1	65	12	179	20
			39.57 to 39.68 - Hematite vein. Coarse magnetite approximately 30%.	61836	75	76	1	75	16	258	10
			39.68 to 42.8 m - Strong k-feldspar alteration, minor hematite.	61837	76	77	1	0.031	31	232	25
				61838	77	78	1	75	16	93	15
42.8	49	Hornblende feldspar breccia	Narrow, 1 cm gouge zone separates hematite bearing rock from above units	61839	78	79	1	30	14	40	20
			Strong, local k-feldspar alteration section at 43 to 45 meters is very hematite rich.	61840	79	80	1	60	11	42	20
				61841	80	81	1	50	17	53	30
			Fine grained, red, mottled foliated with hematite stockwork.	61842	81	82	1	55	21	74	40
			Veined 30 deg. Fractures 45 deg. frs = 20/m vns = 20/m	61843	82	83	1	40	18	61	35
			Weak patchy silica	61844	83	84	1	25	17	53	35
			Moderate pervasive chlorite	61845	84	85	1	40	20	63	50
			Moderate pervasive carbonate	61846	85	86	1	45	25	84	45
			Moderate pervasive magnetite	61847	86	87	1	75	146	152	125
			Moderate pervasive k-spar	61848	87	88	1	120	347	224	320
			Strong stockwork hematite	61849	88	89	1	150	281	230	275
			Weak disseminated pyrite	61850	89	90	1	300	452	648	570
			Quartz microveins	61851	90	90.5	0.5	120	680	665	680
				61852	91	91.5	1	690	679	1500	805
			47.6 to 49 m - limonitic on fractures (broken core)	61853	92	93	1	0.198	1406	3058	10000
				61854	93	94	1	0.712	3511	1877	10000
49	50.29	Semi-Massive Sulfide	Strong pyrite veining, minor arsenopyrite, traces pyrite. Pyrite approximately 30% in dark green chloritic rock - arsenopyrite approximately 5%.	61855	94	94.45	1	0.242	624	726	1760
				61856	94.45	95	1.7	205	31	108	85
			Fine grained, green, veined.	61857	95	96.7	1.7	0.024	16	272	40
			Veins 45 deg. Fractures 45 deg. frs = 5/m vns = 30/m	61858	96.7	97.8	1.1	45	20	16	60
			Weak patchy silica	61859	97.8	99	1.2	110	16	252	95
			Strong, pervasive chlorite	61860	99	100.5	1.5	190	24	174	75
			Weak, pervasive carbonate	61861	100.5	102	1.5	40	12	117	15
			Weak, pervasive k-spar	61862	102	103.5	1.5	80	12	283	10
			Weak, bleb hematite	61863	103.5	105	1.5	0.043	68	244	60
			Intense vein pyrite	61864	105	108.5	1.5	490	59	93	45
				61865	106.5	108	1.5	70	46	35	35
50.29	58.8	Hornblende Feldspar Breccia	Locally, highly chloritic with minor pyrite veinlets up to 5 mm. Local highly k-feldspar altered along one cm veinlets. Minor inclusions of pink hematite-rich calcite. Pyrite from 4-5%. Limonitic on fractures, traces malachite.	61866	108	109.5	1.5	120	42	207	95
				61867	109.5	111	1.5	5	32	193	10
			Medium grained, green. Foliated 45 deg. Fractures 45 deg.	61868	111	112.5	1.5	5	32	250	15
			frs = 30/m vns = 5/m	61869	112.5	114.3	1.5	5	31	203	20
			Weak, patchy silica								
			Moderate, pervasive chlorite								
			Weak patchy carbonate								
			Moderate patchy k-spar								
			Weak patchy hematite								
			Moderate veins pyrite								
			Quartz microveins								
58.8	96.7	Hornblende Feldspar Breccia	60 to 60.6 m. Highly foliated with black chlorite at 30 deg. to C.A.								
			Limonitic on fractures, local strong pink calcite.								
			Hematite occurs as weak to strong zones within the rock unit.								
			60.96 to 69.4 m Strong mosaic textured breccia, foliated at 30 deg. to C.A.								
			Local coarse patches of pyrite								
			Medium grained, red. Mottled, foliated with hematite stockwork.								
			Foliation 45 deg. Veins 35 deg. frs = 15/m vns = 10/m								
			Weak patchy chlorite								

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample No.	Sample Interval		Assay / Geochem			
From	To				From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)
			Moderate pervasive chlorite							
			Weak patchy carbonate							
			Weak patchy magnetite							
			Moderate pervasive k-spar							
			Moderate hematite stockwork							
			Moderate disseminated pyrite							
			Quartz microveins							
			68.96 to 69.3 m. Semi-massive sulfide with 20% pyrite as 5 mm veinlets at 30 deg. to C.A.							
			70.6 to 70.71 m. One cm hematite veinlet at 30 deg. to C.A. with strong magnetite.							
			71 to 76 m. Strong k-spar alteration to light purple color							
			76.3 to 79m. Strong mosaic texture rock with abundant chlorite.							
			75.5 to 91 m. Minor to traces hematite							
			88 to 91.5 m. Strong black chlorite (88.92 - 2 cm massive hematite / minor magnetite veinlet)							
			91.5 to 93 m. Sulfide/hematite vein (coarse pyrite - minor arsenopyrite and hematite). Pyrite up to 50%, arsenopyrite approximately 10%. Section with poor recovery							
			93.3 - 93.35 m. Semi-massive hematite vein at 45 deg. to C.A.							
			93.5 - 94.02 m. Semi-massive sulphide (pyrite from 30-40%, arsenopyrite approx. 10%, minor hematite with traces chalcopyrite)							
			94.1 to 94.15 m. Semi-massive sulphide (pyrite vein).							
			94.45 to 95.7 m. Purple hematite alteration							
96.7	97.85	Diabase Dyke	Fine grained gray. Porphyritic, foliated. Contact 30 deg. fractures 45 deg. frs = 6/m							
97.85	114.3	Hornblende Feldspar Breccia	Moderately strong quartz / calcite stockwork. Local intense k-spar alteration. Mottled, foliated with hematite stockwork. Medium grained, red / green. Veins 45 deg. fractures 45 deg. frs = 5/m vns = 20/m Weak patchy silica Moderate pervasive chlorite Weak patchy magnetite Moderate pervasive k-spar Weak disseminated pyrite Strong quartz calcite microveins							
			98.05 to 98.15 m. Hematite vein, bleached with minor pyrite.							
			99.06 to 100.6 m. Intense k-spar alteration, patches and veinlets of blood red hematite up to 15%. Highly chloritic.							
			100.6 to 107.4 m. Strong k-feldspar alteration with dark chlorite and hematite. Local minor magnetite with hematite veinlets.							
			107.4 to 114.3 m. Local intense k-feldspar, locally strongly chloritic, minor hematite as veinlets.							
			E.O.H. 114.3 m.							

TEUTON RESOURCES CORPORATION LTD.

PROPERTY: Clone Property					HOLE No. DDH-CI-97-128							
Azimuth: 160 deg.		Dip: 50 deg.		Depth: 131.06m		Date:		Logged by: ERK				
Meterage From	To	Rock Type	Alteration, Mineralization & Structure Description	Sample No.	Sample Interval		Assay / Geochem					
					From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)	
1.22	9.8	Hornblende Feldspar Breccia	Locally intense hematite stockwork, variably k-feldspar altered. Weak quartz calcite veinlets, minor local calcite/chlorite veinlets. Limonitic on fractures.	59802	1.22	3	1.78	0.039	53	67	60	
				Mottled foliated with hematite stockwork.	59803	3	4.8	1.8	230	44	21	40
				Medium grained, red. Veined 30 deg. fractures 45 deg. frs = 8/m	59804	4.8	6	1.2	0.059	32	38	15
				vns = 20/m	59805	6	7.5	1.5	45	18	28	20
				Moderate patchy silica	59806	7.5	9	1.5	330	89	226	150
				Strong pervasive chlorite	59807	9	10.5	1.5	30	28	134	35
				Moderate pervasive carbonate	59808	10.5	12	1.5	50	41	402	55
				Moderate pervasive k-spar	59809	12	13.5	1.5	40	25	83	40
				Strong hematite stockwork	59810	13.5	15	1.5	45	14	99	30
				Moderate veined pyrite	59811	15	16.6	1.5	40	13	175	70
				Quartz microveins	59812	16.5	18	1.5	90	13	72	50
					59813	18	19.5	1.5	110	17	121	35
					59814	19.5	21	1.5	70	21	208	35
				2.9 to 3.7 - intense hematite approx. 50%	59815	21	22.5	1.5	60	18	58	25
				5 to 5.3 m - pyrite veinlets up to 5 mm with local dark green / black chlorite.	59816	22.5	24	1.5	50	24	53	65
				Pyrite approx. 15%	59817	24	25.5	1.5	170	35	44	75
				8.3 to 8.8 m - very strong k-feldspar alteration to pink, dark green mottled rock.	59818	25.5	27	1.5	5	11	67	30
					59819	27	28.5	1.5	5	10	36	35
9.8	11.8		Hornblende Feldspar Breccia	Minor hematite rich calcite stringers.	59820	28.5	30	1.5	10	12	42	90
				Foliated, brecciated	59821	30	31.5	1.5	5	13	63	40
				Medium grained green. Foliation 45 deg., fractures 35 deg. frs = 6/m,	59822	31.5	33	1.5	5	15	82	70
				vns = 3/m	59823	33	34.5	1.5	10	12	88	70
				Weak patchy silica	59824	34.5	36	1.5	5	13	88	45
				Moderate pervasive chlorite	59825	36	37.5	1.5	55	26	186	130
				Moderate pervasive carbonate	59826	37.5	39	1.5	80	32	157	170
				Weak pervasive k-spar	59827	39	40	1	20	48	170	205
				Weak patchy hematite	59828	40	41	1	25	45	165	200
				Moderate disseminated pyrite	59829	41	42	1	120	91	142	695
				Quartz microveins	59830	42	43	1	0.093	502	264	7025
					59831	43	44	1	385	269	243	2370
11.8	19.2	Hornblende Feldspar Crystalline		Local k-feldspar alteration, minor narrow pyrite veinlets, locally limonitic on fractures. Crystalline medium grained green. Veined 30 deg. fractures 45 deg. frs = 6/m, vns = 3/m.	59832	44	45	1	0.326	643	757	960
					59833	45	46	1	790	139	220	200
				Weak patchy silica	59834	46	47.5	1.5	205	34	233	65
				Moderate pervasive chlorite	59835	47.5	49	1.5	515	57	201	85
				Moderate pervasive carbonate	59836	49	50.5	1.5	35	30	67	40
				Moderate pervasive k-spar	59837	50.5	52	1.5	0.034	209	284	250
				Moderate disseminated pyrite	59838	52	53.5	1.5	0.081	118	122	150
				Quartz microveins	59839	53.5	55	1.5	0.042	78	359	110
					59840	55	56.5	1.5	505	21	519	30
					59841	56.5	58	1.5	800	25	461	35
19.2	21.95	Hornblende Feldspar Breccia	Mottled red/green, local intense k-feldspar alteration. Mottled, foliated hematite stockwork. Medium grained, red. Foliated 30 deg. fractures 45 deg. frs = 5/m, vns 15/m	59842	58	59.5	1.5	205	18	244	35	
					59843	59.5	61	1.5	75	19	233	35
				Weak patchy silica	59844	61	62.5	1.5	155	58	110	125
				Moderate pervasive chlorite	59845	62.5	64	1.5	0.041	70	175	80
				Moderate pervasive carbonate	59846	64	65.5	1.5	0.089	176	310	210
				Moderate pervasive k-spar	59847	65.5	66.75	1.25	155	614	423	350
				Moderate hematite stockwork	59848	66.75	68	1.25	0.404	917	1581	380
				Moderate disseminated pyrite	59849	68	68.89	0.69	1.219	970	3768	740
				Quartz microveins	59850	68.89	69.64	1.03	370	434	631	450
					59851	69.64	70.7	1.03	0.289	981	295	750
					59852	70.7	72	1.03	0.046	93	157	75
21.95	42.67		Hornblende Feldspar Breccia	Variably mottled, due to weak foliation (black chlorite wisps). Local k-feldspar alteration. Minor 1 cm wide calcite/hematite veinlets. Mottled, veined, foliated. Medium grained, green. Veined 80 deg., fractures 60 deg. frs = 6/m vns = 10/m	59853	72	73.5	1.5	0.106	56	600	115
					59854	73.5	75	1.5	805	39	102	50
				Weak patchy silica	59855	75	76.5	1.5	0.037	73	154	70
					59856	76.5	78	1.5	40	23	140	15
				59857	78	79.5	1.5	215	25	125	20	

Meterage From To	Rock Type	Alteration, Mineralization & Structure Description	Sample No.	Sample Interval		Assay / Geochem				
				From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
		Moderate pervasive chlorite	59858	79.5	81	1.5	260	42	181	45
		Moderate pervasive carbonate	59859	81	82.5	1.5	15	19	145	30
		Weak patchy magnetite	59860	82.5	84	1.5	205	67	100	90
		Moderate pervasive k-spar	59861	84	85.5	1.5	225	73	256	80
		Weak patchy hematite	59862	85.5	87	1.5	780	80	204	80
		Moderate disseminated pyrite	59863	87	88.5	1.5	220	63	200	65
		Quartz microveins	59864	88.5	90.5	2	270	121	173	115
			59865	90.5	91.5	1	0.246	1686	1642	1695
		33.8 to 33.95 m - narrow pyrite veinlets approx. 7-8 mm wide	59866	91.5	92.5	1	0.078	352	1114	375
		34.7 m - strongly magnetic over 6 cm zone. Magnetite veinlets approx. 3-4 mm in k-feldspar altered zone. Pervasive quartz calcite stockwork approx. 5%.	59867	92.5	93.3	0.8	0.033	576	248	715
			59868	93.3	94	0.7	0.989	2711	3458	3540
		41 to 42.67 m - numerous fractures filled with pyrite. Veinlets approx. 1-2 mm with pyrite approx. 7 to 8% overall.	59869	94	95.5	1.5	865	549	701	680
			59870	95.5	97.56	2.06	215	80	149	95
		42 to 42.67 m - arsenopyrite approx. 5% as veinlets with pyrite and as coarse blebs	61870	97.56	99	1.44	575	26	122	20
			61871	99	100.5	1.5	35	9	2562	10
			61872	100.5	102	1.5	5	9	484	5
42.67	58.3	Hornblende Feldspar Breccia	61873	102	103.5	1.5	35	7	22	10
		Variably mottled red/green. Local strong k-feldspar alteration with associated black chlorite. Foliated, veined with hematite stockwork. Medium grained, red	61874	103.58	105	1.5	10	11	7	10
		Veins 60 deg., fractures 45 deg. frs = 7/m, vns = 15/m.	61875	105	106.5	1.5	10	12	11	5
		Weak patchy silica	61876	106.5	108	1.5	40	26	791	15
		Moderate pervasive chlorite	61877	108	109.5	1.5	5	30	330	15
		Moderate pervasive carbonate	61878	109.5	111	1.5	5	28	38	20
		Moderate patchy magnetite	61879	111	112.5	1.5	5	32	153	30
		Moderate pervasive k-spar	61880	112.5	114	1.5	30	38	202	25
		Strong hematite stockwork	61881	114	115.5	1.5	5	30	137	10
		Weak disseminated pyrite	61882	115.5	117	1.5	360	131	407	90
		Quartz microveins	61883	117	118.5	1.5	180	29	154	5
			61884	118.5	120	1.5	10	30	151	10
		44 to 45 m - strongly magnetic with minor pyrite.	61885	120	121	1	105	53	178	30
		51 to 55 m - narrow hematite stringers with magnetite, veinlets approx. 10%.	61886	121	122	1	65	40	121	200
			61887	122	123	1	35	23	135	15
58.3	66.75	Hornblende Feldspar Breccia	61888	123	124.4	1.4	5	29	91	10
		Rock appears to be autobrecciated with all similar clasts in a dark green chlorite rich matrix. Minor 1 cm wide chlorite veinlets. Foliated brecciated	61889	124.4	126.36	1.94	5	14	11	15
		fragmental, sheared. Clasts, green. Foliated 30 deg., fractures 15 deg.	61890	126.36	128	1.64	5	37	136	10
		frs = 20/m, vns = 4/m.	61891	128	128.5	1.5	5	36	135	35
		Weak patchy silica	61892	128.5	131.06	2.1	5	36	145	25
		Strong pervasive chlorite								
		Moderate pervasive carbonate								
		Moderate pervasive k-spar								
		Weak patchy hematite								
		Moderate disseminated pyrite								
		Quartz microveins								
		59.5 to 66.75 m - broken core, limonitic on fractures.								
66.75	70.7	Semi Massive Hematite								
		Zone consists of 50% hematite with associated strong magnetite, minor pyrite. Veined, red.								
		66.75 to 68.69 m - massive hematite, minor malachite with limonite on fractures.								
		69.64 to 70.25 m - massive hematite, with up to 10% magnetite.								
70.7	90.5	Hornblende Feldspar Breccia								
		Locally, autobrecciated, same as 58.3 to 66.75 m. Local strong k-feldspar alteration. Foliated, brecciated fragmental, mottled. Clasts, green. Foliation								
		30 deg., fractures 45 deg. frs = 10/m, vns = 5/m.								
		Weak patchy silica								
		Strong pervasive chlorite								
		Moderate pervasive carbonate								
		Moderate pervasive k-spar								
		Moderate patchy hematite								

TEUTON RESOURCES CORPORATION LTD.

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample No.	Sample Interval		Assay / Geochem					
From	To				From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)	
			Moderate disseminated pyrite Quartz microveins									
			84.2 to 84.8 m - calcite vein at 15 deg. to C.A. Local patches of coarse pyrite.									
90.5	94.49	Semi Massive Hematite	Local calcite/chlorite veins up to 4 cm. Veined, mottled. Medium grained, red. Veins 45 deg., fractures 45 deg., frs = 6/m, vns = 15/m. Weak, patchy silica Strong pervasive chlorite Moderate pervasive carbonate Strong pervasive magnetite Strong pervasive k-spar Intense vein hematite Weak disseminated pyrite Quartz microveins									
			90.7 to 90.85 m - strong magnetite in massive hematite vein									
			91.8 to 91.8 m - semi massive hematite									
			93.4 to 94 m - massive hematite with strong patches of magnetite approx. 10%									
94.49	124.4	Hornblende Feldspar Breccia	Limonitic on fractures up to 97.56 m. Local intense k-feldspar with wispy, blood red hematite. Local strong chlorite, generally patchy hematite stockwork. Mottled, foliated with hematite stockwork. Medium grained, green. Veins 20 deg., fractures 45 deg. frs = 6/m, vns = 6/m. Weak patchy silica Strong pervasive chlorite Weak pervasive carbonate Moderate pervasive k-spar Weak hematite stockwork Weak disseminated pyrite Quartz microveins									
			97.9 to 98.02 m - semi massive hematite with 15% hematite, strong chlorite									
			99 m - 2 cm semi massive hematite vein									
			99 to 100.7 m - strong mosaic texture with fragments approx. 1-2 cm in chloritic matrix. Fragments approx. 90%.									
			102.4 to 104 m - mosaic texture									
			110.4 m - patches of green chlorite with calcite up to 6 cm across									
			114 to 120.5 m - strong k-feldspar alteration with wispy veinlets and narrow veins of hematite up to 15%. Minor magnetite with hematite veinlets, strongly chloritic.									
			120.85 to 121.6 m - strong pyrite veinlets with hematite, locally vuggy where calcite has dissolved from veins. Strong green chlorite with pyrite veinlets, pyrite approx. 20%.									
			122.4 to 124.2 m - strong k-feldspar alteration with strong chlorite and approx. 10% hematite in the wispy veinlets									
124.4	126.34	Diabase Dyke	Porphyritic, brown. Fractures 45 deg., contact 30 deg. frs = 5/m, vns = 1/m.									
126.34	131.06	Hornblende Feldspar Breccia	127.6 m - 5 mm calcite/pyrite veinlet in 6 cm zone with approx. 5% pyrite Mottled, wispy with hematite stockwork. Medium grained red/green. Veins 30 deg., fractures 30 deg., frs = 3/m, vns = 15/m. Weak patchy silica Moderate pervasive chlorite Moderate pervasive k-spar Moderate hematite stockwork Moderate disseminated pyrite Quartz/calcite microveins									
			E.O.H. 131.06 m									

TEUTON RESOURCES CORPORATION LTD.

PROPERTY: Clone Property				HOLE No. DDH-CI-97-129							
Azimuth: 185		Dip: -60 deg		Depth: 76.2 m				Date:		Logged by: ERK	
Meterage From To	Rock Type	Alteration, Mineralization & Structure Description	Sample No.	Sample Interval		Assay / Geochem					
				From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)	
1.52	8.05	Hornblende Feldspar Breccia	Locally, strong k-feldspar altered, brecciated with local narrow sections with black chlorite. Narrow 5 mm veinlets with calcite/chlorite veinlets. Mottled, foliated with hematite stockwork. Medium grained, red. Foliated 30 deg., veins 50 deg., fra = 3/m, vns = 10/m.	59871	1.52	3	1.48	315	44	30	15
				59872	3	4.5	1.5	0.029	68	34	85
				59873	4.5	6	1.5	0.361	44	53	5
				59874	6	7.5	1.5	230	20	55	10
				59875	7.5	9	1.5	415	91	549	135
				59876	9	10.5	1.5	55	28	184	65
				59877	10.5	12	1.5	30	37	143	85
				59878	12	13.5	1.5	25	23	168	45
				59879	13.5	15	1.5	10	31	130	70
				59880	15	16.5	1.5	5	18	47	40
				59881	16.5	18	1.5	5	11	80	35
				59882	18	19.5	1.5	80	18	381	35
8.05	13.7	Hornblende Feldspar Breccia	Mottled, foliated. Medium grained, green. Foliated 45 deg., fractures 50 deg. fra = 8/m, vns = 3/m.	59883	19.5	21	1.5	45	21	586	35
				59884	21	22.5	1.5	5	9	28	10
				59885	22.5	24	1.5	5	7	20	10
				59886	24	25.5	1.5	5	7	25	20
				59887	25.5	27	1.5	5	8	15	16
				59888	27	28.5	1.5	5	8	32	15
				59889	28.5	30	1.5	5	7	7	20
				59890	30	31.5	1.5	10	11	35	40
				59891	31.5	33	1.5	5	11	51	225
				59892	33	34.5	1.5	5	10	39	270
				59893	34.5	36	1.5	5	9	83	110
				59894	36	37.5	1.5	95	8	84	35
				59895	37.5	39	1.5	10	6	15	35
13.7	37.3	Hornblende Feldspar Crystalline	Local intense k-feldspar alteration over 30 cm sections. Traces hematite as wisps. Crystalline. Medium grained, green. Veins 45 deg., fractures 45 deg., fra = 3/m, vns = 2/m.	59896	39	40.5	1.5	130	10	67	15
				59897	40.5	42	1.5	5	10	88	60
				59898	42	43.5	1.5	10	11	104	80
				59899	43.5	45	1.5	10	10	111	35
				59900	45	46.5	1.5	195	17	249	60
				59901	46.5	48	1.5	55	14	205	40
				59902	48	49.5	1.5	60	14	175	35
				59903	49.5	51	1.5	300	33	886	45
				59904	51	62.6	1.5	215	93	276	120
				59905	52.5	54	1.5	345	148	220	240
				59906	54	55.5	1.5	125	115	132	195
				59907	55.5	57	1.5	335	87	364	125
				59908	57	58	1	30	155	132	145
				59909	58	59	1	1000	233	444	280
37.3	76.2	Hornblende Feldspar Breccia	Intense quartz calcite stockwork up to 15%. Mottled foliated. Medium grained, green. Veins 45 deg., fractures 45 deg., fra = 3/m, vns = 8/m.	59910	59	60.5	1.5	145	118	144	120
				59911	60.5	62	1.5	265	118	103	125
				59912	62	63.5	1.5	115	60	118	45
				59913	63.5	65	1.5	385	139	25	90
				59914	65	66.5	1.5	15	43	8	30
				59915	66.5	68	1.5	110	18	20	20
				59916	68	69.5	1.5	30	10	65	10
				59917	69.5	71	1.5	5	7	4	15
				59918	71	72.5	1.5	10	6	7	10
				59919	72.5	74	1.5	15	6	2	5
				59920	74	76.2	2.2	15	5	3	5
			37.3 to 39.9 m - local narrow 5 mm pyrite veinlets								
			From 42 m, local sections of intense k-feldspar alteration.								
			55.4m - narrow calcite veinlets with magnetite crystals								
			58 to 59 m - narrow massive magnetite veinlets up to 5 mm								
			61.9 to 64.2 m - broken core								
			66.3 to 68.4 m - calcite veining								
			75.9 to 76.15 m - calcite veinlet/chlorite patches								

PROPERTY: Clone Property						HOLE No.	DDH-CI-97-130			
Azimuth:245 degrees			Dip: -65 degree	Depth:167.64 m		Date:			Logged by:ERK	
Meterage		Rock Type	Alteration, Mineralization	Sample	Sample	Interval	Assay / Geochem			
From	To		& Structure Description	No.	From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)
1.52	93	Hornblende Feldspar Breccia	Zone of intense hematite alteration. Local intense k-feldspar alteration.	59921	1.52	3	1.48	10	11	28
			Numerous quartz/calcite/chlorite veinlets. Some quartz/calcite veinlets up to 3 cm. Veining up to 8%. Minor epidote as selvages to veinlets. Overall mottled red/green.	59922	3	4	1	20	8	14
			Mottled, veined, wispy, stockwork. Medium grained, red. Veins 75 deg., fractures 75 deg., frs = 2/m, vns = 10/m.	59923	4	5	1	45	33	18
			Moderate patchy silica	59924	5	6	1	10	66	30
			Moderate pervasive chlorite	59925	6	7	1	615	40	42
			Moderate pervasive carbonate	59926	7	8	1	20	17	26
			Moderate pervasive k-spar	59927	8	9	1	10	16	8
			Strong hematite stockwork	59928	9	10	1	15	20	157
			Weak specularite veins	59929	10	11.5	1.5	45	29	14
			Weak disseminated pyrite	59930	11.5	13	1.5	150	25	51
			Quartz microveins	59931	13	14.5	1.5	10	27	337
				59932	14.5	16	1.5	5	25	803
				59933	16	17.5	1.5	5	16	25
				59934	17.5	18.5	1	10	14	32
				59935	18.5	20	1.5	5	9	15
			1.52 to 10 m - H - 2 zone. Subtle zone of hematite alteration with narrow 5 mm stringers of blood red hematite. Sections of numerous chlorite bearing veinlets. Sections over 30 cm wide.	59936	20	21.5	1.5	5	13	3
				59937	21.5	23	1.5	40	13	15
				59938	23	24.5	1.5	5	11	14
			18.3 to 18.4 m - specularite veinlets approx. 15%.	59939	24.5	26	1.5	5	6	22
			47 m - definite decrease in hematite content.	59940	26	27.5	1.5	5	14	5
			59.7 to 59.9 m - narrow calcite/pyrite veinlet approx. 1 cm wide parallel to core axis	59941	27.5	29	1.5	15	9	8
				59942	29	30.5	1.5	16	7	87
			59.9 m - strong k-feldspar alteration with minor blood red stringers	59943	30.5	32	1.5	50	11	45
			65 to 65.2 m - coarse pyrite veinlets, pyrite approx. 20%	59944	32	33.5	1.5	40	14	26
			68.05 to 68.15 m - narrow pyrite veinlets in intense k-feldspar alteration	59945	33.5	35	1.5	45	10	8
			69.7 to 71.5 m - intense k-feldspar alteration to tan rock. Minor pyrite veinlets with dark green chlorite. Locally highly silicified.	59946	35	36.5	1.5	305	17	8
				59947	36.5	38	1.5	315	20	8
			71.6 to 71.8 m - marcasite? on fractures. Sulfides approx. 10%.	59948	38	39.5	1.5	45	20	10
			74.5 to 76.2 m - intense k-feldspar alteration with blebs and veinlets of pyrite approx. 5%. Minor quartz/calcite/chlorite veinlets.	59949	39.5	41	1.5	5	7	60
				59950	41	42.5	1.5	5	7	18
				59951	42.5	44	1.5	10	8	43
93	124	Hornblende Feldspar Breccia	Locally mosaic breccia texture with fragments up to 4 cm in a black chlorite matrix. Quartz/calcite veinlets approx. 3-4%. Mottled, foliated. Medium grained, green. Veins 60 deg., fractures 70 deg., frs = 3/m, vns = 4/m.	59952	44	45.5	1.5	285	23	19
				59953	45.5	47	1.5	65	21	16
				59954	47	48.5	1.5	5	10	44
			Moderate patchy silica	59955	48.5	50	1.5	5	8	183
			Strong pervasive chlorite	59956	50	51.5	1.5	0.036	42	21
			Moderate pervasive carbonate	59957	51.5	53	1.5	5	20	19
			Moderate pervasive k-spar	59958	53	54.5	1.5	10	9	146
			Weak wispy hematite	59959	54.5	56	1.5	5	10	161
			Moderate disseminated pyrite	59960	56	57.5	1.5	5	6	29
			Quartz calcite microveins	59961	57.5	59	1.5	5	6	16
				59962	59	60.5	1.5	155	9	63
			93.3 to 93.4 m - calcite vein	59963	60.5	62	1.5	5	7	31
			105.72 to 108.68 m - H - 1 zone. Generally weak zone of k-feldspar alteration with local patches, fracture filling and veinlets of pyrite, weak wispy hematite with the pyrite veinlets. Sulfide closely associated with sections of k-feldspar alteration. Veined. Medium grained, green. Veins 60 deg., fractures 60 deg., frs = 4/m, vns = 10/m.	59964	62	63.5	1.5	5	9	27
				59965	63.5	65	1.5	5	8	14
				59966	65	66.5	1.5	5	19	23
				59967	66.5	68	1.5	0.067	141	84
				59968	68	69.5	1.5	0.086	111	50
			Moderate patchy silica	59969	69.5	71	1.5	55	46	84
			Moderate pervasive chlorite	59970	71	72.5	1.5	60	12	97
			Strong pervasive k-spar	59971	72.5	74	1.5	10	10	36
			Weak wispy hematite	59972	74	75.5	1.5	5	11	304
			Moderate vein pyrite	59973	75.5	77	1.5	5	8	205

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample	Sample	Interval	Assay / Geochem			
From	To			No.	From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)
			Quartz calcite microveins	59974	77	78.5	1.5	5	8	28
				59975	78.5	80	1.5	5	8	55
			108.68 to 120.05 m - zone of weak k-feldspar alteration with local narrow pyrite veinlets	59976	80	81.5	1.5	20	9	16
				59977	81.5	83	1.5	5	7	71
			120.05 to 124 m - H - 1 zone. Moderately strong zone of intense black chlorite, massive pyrite veins, wisps and fracture filling with minor wisps of hematite, minor arsenopyrite and traces chalcopyrite.	59978	83	84.5	1.5	5	10	75
				59979	84.5	86	1.5	5	16	64
				59980	86	87.5	1.5	5	13	91
			121.89 to 122.05 m - massive pyrite/minor arsenopyrite	59981	87.5	89	1.5	10	12	81
				59982	89	90.5	1.5	5	12	46
			122.9 to 122.92 m - massive pyrite	59983	90.5	92	1.5	5	9	14
			122.98 to 123.2 m - semi massive pyrite/arsenopyrite	59984	92	93.5	1.5	25	75	90
124	153.74	Hornblende Feldspar Breccia	Foliated, sericite rich section with strong quartz/calcite stockwork approx. 10%. Fine disseminated pyrite approx. 5%. Local pink calcite veinlets.	59985	93.5	95	1.5	5	12	38
			Locally section is highly crenulated. Foliated, mottled. Medium grained, gray.	59987	97	98.5	1.5	5	12	67
			Foliated 45 deg., veined 60 deg., frs = 4/m, vns = 15/m.	59988	98.5	100	1.5	5	12	85
			Weak patchy silica	59989	100	101.5	1.5	100	14	70
			Moderate pervasive chlorite	59990	101.5	103	1.5	5	10	89
			Moderate pervasive sericite	59991	103	104.5	1.5	15	11	75
			Moderate pervasive k-spar	59992	104.5	105.72	1.22	10	10	82
			Moderate disseminated pyrite	59993	105.72	107	1.28	55	17	171
			Quartz calcite microveins	59994	107	108.68	1.68	340	43	965
				59995	108.68	110	1.32	15	12	136
			Locally rocks are k-feldspar altered to tan color.	59996	110	111	1	10	10	70
			138.1 to 139.3 m - fine grained pyrite approx. 10%	59997	111	112	1	10	11	20
			139.5 to 144 m - strong quartz calcite stockwork approx. 15%	59998	112	113	1	40	12	14
				59999	113	114	1	60	13	17
153.74	155.87	Hornblende Feldspar Breccia	S - 2A zone. Mottled, foliated, veined. Medium grained, light gray. Veins 40 deg., fractures 45 deg., frs = 3/m, vns = 10/m.	60000	114	115	1	120	9	16
			Moderate patchy silica	60001	115	116	1	55	8	19
			Moderate pervasive chlorite	60002	116	117	1	5	14	8
			Weak pervasive sericite	60003	117	118	1	5	12	14
			Moderate pervasive k-spar	60004	118	119	1	5	19	15
			Strong vein pyrite	60005	119	120	1	15	16	12
			Quartz calcite microveins	60006	120	121	1	65	29	15
				60007	121	121.89	0.89	70	12	128
				60008	121.89	124	2.11	0.068	76	1556
			153.79 to 154 m - zone of black chlorite with pyrite/arsenopyrite stringers	60009	124	125	1	5	41	225
			155.3 to 155.65 m - pyrite/arsenopyrite veinlets	60010	125	126.5	1.5	10	35	182
			Overall, pyrite/arsenopyrite approx. 7%.	60011	126.5	128	1.5	25	34	184
				60012	128	129.5	1.5	10	33	130
155.87	164.1	Hornblende Feldspar Breccia	Generally, bleached light green, locally highly sheared with strong quartz calcite stockwork. Mottled, brecciated. Medium grained, green. Veins 45 deg., fractures 60 deg., frs = 10/m, vns = 5/m.	60013	129.5	131	1.5	5	30	188
			Moderate patchy silica	60014	131	132.5	1.5	5	31	199
			Moderate pervasive chlorite	60015	132.5	134	1.5	5	36	148
			Moderate pervasive sericite	60016	134	135.5	1.5	5	32	101
			Moderate pervasive k-spar	60017	135.5	137	1.5	5	33	88
			Moderate disseminated pyrite	60018	137	138.1	1.1	15	34	103
			Quartz calcite microveins	60019	138.1	139.3	1.2	25	33	137
				60020	139.3	141	1.7	5	37	119
				60021	141	142.5	1.5	5	33	88
			158.05 to 158.1 m - calcite vein	60022	142.5	144	1.5	55	58	91
			161 to 161.1 m - calcite vein	60023	144	145.5	1.5	10	36	199
			158.5 to 160 m - broken core. Sheared, minor gouge, abundant chlorite on slip faces.	60024	145.5	147	1.5	985	55	145
				60025	147	148.5	1.5	10	38	153
			163.4 to 164 m - broken core. Strong fault zone with gouge.	60026	148.5	150	1.5	30	34	152
				60027	150	151.5	1.5	35	40	204
				60028	151.5	153	1.5	30	61	236
164.1	167.64	Mudstone	Highly sheared, graphitic with coarsely crystalline calcite veinlets up to 2 cm parallel to core axis. In non-sheared portion, strong calcite stockwork with	60029	153	153.79	0.79	10	35	96
				60030	153.79	154.33	0.54	165	77	77

PROPERTY: Clone Property				HOLE No.		DDH-CI-97-131						
Azimuth: 245 degrees		Dip: -62 degrees		Depth: 131.06 m		Date:		Logged by: ERK				
Meterage		Rock Type		Alteration, Mineralization		Sample		Assay / Geochem				
From	To	& Structure Description		No.	From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)	
0.61	89	Hornblende Feldspar Breccia		Mottled, red/green with local intense k-feldspar alteration. Numerous quartz calcite veinlets approx. 1-4 mm wide, some with dark green chlorite. Local vugs along the veinlets. Epidote common along quartz veinlets. Mottled, veined, hematite stockwork. Medium grained, red. Veins 45 deg., fractures 30 deg., frs = 5/m, vns = 15/m.	60036	0.61	2	1.38	5	16	24	30
				60037	2	3	1	5	10	26	20	
				60038	3	4	1	25	22	13	15	
				60039	4	5	1	75	41	38	15	
				60040	5	6	1	20	22	176	15	
				60041	6	7	1	5	15	12	10	
				60042	7	8	1	5	12	31	15	
				60043	8	9	1	5	14	11	15	
				60044	9	10	1	5	18	8	35	
				60045	10	11	1	5	14	15	10	
				60046	11	12	1	5	16	15	25	
				60047	12	13.5	1.5	10	23	15	25	
				60048	13.5	15	1.5	5	16	65	20	
				60049	15	16.5	1.5	40	17	120	20	
				60050	16.5	18	1.5	10	11	18	20	
				60051	18	19.5	1.5	25	14	8	10	
				60052	19.5	21	1.5	75	23	6	10	
				60053	21	22.5	1.5	85	24	12	20	
				60054	22.5	24	1.5	80	30	23	10	
				60055	24	25.5	1.5	85	52	13	15	
				60056	25.5	27	1.5	5	10	18	10	
				60057	27	28.5	1.5	30	9	10	10	
				60058	28.5	30	1.5	25	9	11	10	
				60059	30	31.5	1.5	15	10	65	15	
				60060	31.5	33	1.5	75	9	74	25	
				60061	33	34.5	1.5	10	9	11	5	
				60062	34.5	36	1.5	10	10	15	10	
				60063	36	37.5	1.5	25	10	14	15	
				60064	37.5	39	1.5	5	13	25	10	
				60065	39	40.5	1.5	5	17	47	5	
				60066	40.5	42	1.5	5	12	68	15	
				60067	42	43.5	1.5	10	38	24	20	
				60068	43.5	45	1.5	15	27	28	10	
				60069	45	48.5	1.5	5	10	151	5	
				60070	46.5	48	1.5	10	8	15	10	
				60071	48	49.5	1.5	30	7	20	15	
				60072	49.5	51	1.5	5	8	48	5	
				60073	51	52.5	1.5	40	8	27	5	
				60074	52.5	54	1.5	55	5	11	25	
				60075	54	55.5	1.5	5	9	148	20	
				60076	55.5	57	1.5	5	9	144	30	
				60077	57	58.5	1.5	5	15	46	5	
				60078	58.5	60	1.5	55	31	24	25	
				60079	60	61.5	1.5	25	9	69	25	
89	94.49	Hornblende Feldspar Breccia		H - 1 zone. Zone of intense black chlorite, massive sulfide veins and hematite	60080	61.5	63	1.5	5	9	75	20
				Veined, foliated. Medium grained, green. Veins 45 deg., fractures 45 deg., frs = 3/m, vns = 20/m.	60081	63	64.5	1.5	5	15	314	30
				60082	64.5	66	1.5	5	10	151	35	
				60083	66	67.5	1.5	250	13	232	50	
				60084	67.5	69	1.5	85	10	191	15	
				60085	69	70.5	1.5	60	10	198	5	
				60086	70.5	72	1.5	40	15	139	10	
				60087	72	73	1	115	13	81	15	
				60088	73	73.92	0.9	5	12	81	10	
				60089	73.92	75	1.08	5	8	61	10	
				60090	75	76.5	1.5	10	10	82	20	

TEUTON RESOURCES CORPORATION LTD.

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample	Sample	Interval	Assay / Geochem				
From	To			No.	From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
			91.25 to 90.7 m - massive pyrite, minor arsenopyrite, traces chalcopyrite, strongly magnetic	60091	76.5	78	1.5	40	10	124	25
			92.5 to 92.6 m - pyrite, minor arsenopyrite and hematite	60092	78	79.5	1.5	60	10	190	20
			93.65 to 93.85 m - predominantly pyrite, minor arsenopyrite	60093	79.5	81	1.5	145	16	193	20
			93.95 to 94 m - calcite vein associated with light green chlorite	60094	81	82.93	1.5	30	24	69	20
			94.12 to 94.28 m - pyrite/arsenopyrite vein	60095	82.93	84	1.07	0.053	97	241	115
				60096	84	85.5	1.5	315	41	103	55
				60097	85.5	87	1.5	75	19	141	30
94.49	105.3	Hornblende Feldspar Breccia	Local narrow black chlorite patches, local minor narrow veinlets of pyrite. Mottled, veined. Fine grained, green. Fractures 30 deg., veins 45 deg., frs = 4/m, vns = 6/m.	60098	87	88	1	30	28	143	55
			Weak patchy silica	60099	88	89	1	155	48	130	80
			Moderate pervasive chlorite	60100	89	90	1	30	234	182	300
			Moderate pervasive carbonate	60101	90	91	1	0.342	1753	3885	1.23
			Weak pervasive k-spar	60102	91	92	1	975	593	855	845
			Moderate disseminated pyrite	60103	92	93	1	0.068	425	1237	1265
			Quartz calcite microveins	60104	93	93.65	0.65	115	64	90	325
				60105	93.65	94.49	0.84	0.216	794	1646	4780
				60106	94.49	95	0.51	350	50	166	180
				60107	95	96.5	1.5	30	13	67	25
105.3	107.81	Hornblende Feldspar Breccia	H - 1 zone. Zone of black chlorite, massive sulfide veins, minor hematite and quartz/k-spar veins. Veined, mottled. Fine grained, green. Veins 45 deg., fractures 45 deg., frs = 4/m, vns = 10/m.	60108	96.5	98	1.5	10	10	46	20
			Weak patchy silica	60109	98	99.5	1.5	5	13	39	55
			Strong pervasive chlorite	60110	99.5	101	1.5	10	16	115	105
			Moderate pervasive carbonate	60111	101	102.5	1.5	65	26	140	150
			Weak patchy magnetite	60112	102.5	104	1.5	30	12	145	45
			Weak pervasive k-spar	60113	104	105.3	1.2	20	20	184	65
			Intense vein pyrite	60114	105.3	105.91	0.61	0.895	1096	4658	1.32
			Quartz calcite microveins	60115	105.91	107	1.09	470	149	411	1480
				60116	107	107.81	0.81	1.097	2182	3704	3.03
				60117	107.81	108.5	0.7	255	21	105	155
				60118	108.5	110	1.5	75	17	30	180
			105.3 to 105.91 m - predominantly massive pyrite, minor arsenopyrite, magnetite veinlet 1 cm wide as well as minor hematite	60119	110	111.5	1.5	5	14	25	70
			107 to 107.81 m - strong arsenopyrite with massive pyrite and wisps of hematite	60120	118	119	1	15	15	73	70
				60121	119	120	1	25	18	112	40
				60122	120	121	1	25	14	108	30
				60123	121	122	1	415	80	724	1025
107.81	131.06	Hornblende Feldspar Breccia	Weakly foliated, minor black chlorite patches. Mottled, foliated. Fine grained green. Fractures 45 deg., veins 30 deg., frs = 4/m, vns = 2/m.	60124	122	123	1	110	32	243	65
			Weak patchy silica	60125	123	124	1	5	41	178	35
			Moderate pervasive chlorite	60126	124	125	1	15	39	172	25
			Moderate patchy sericite	60127	125	126	1	5	27	195	25
			Weak pervasive k-spar	60128	126	127	1	40	32	149	45
			Weak disseminated pyrite	60129	127	128	1	5	36	181	50
			Quartz calcite microveins	60130	128	129	1	15	33	206	50
			112 to 118.3 m - strong wuggy calcite veins up to 4 cm wide, generally 30 deg. to C.A. Abundant bladed calcite crystals in stockwork approx. 20% of section.								
			116.74 to 117.9 m - limonitic								
			122.3 to 122.6 m - shear zone at 45 deg. to C.A.								
			123.5 to 126.5 m - S - 2a zone? Weak pyrite veinlets approx. 7% with local black chlorite.								
			From 129 m to 131.06 m - strong sericite alteration								
			130.1 to 130.4 m - shear zone (gouge and clay) at 45 deg. to C.A.								
			E.O.H. 131.06 m								

TEUTON RESOURCES CORPORATION LTD.

PROPERTY: Clone Property				HOLE No.		DDH-CI-97-132						
Azimuth: 230 degrees		Dip: -65 degree		Depth: 143.26 m		Date:		Logged by: ERK				
Meterage		Rock Type		Alteration, Mineralization		Sample		Assay / Geochem				
From	To	& Structure Description		No.	From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)	
				60131	1	3	2	5	12	37	15	
0.31	88.8	Homblende Feldspar Breccia		Mottled red/green, locally intense k-feldspar alteration, local quartz/ calcite/ chlorite veinlets up to 5 mm. Some quartz/calcite veinlets have epidote as selvages.	60132	3	4	1	10	14	15	
				60133	4	5	1	10	20	116	10	
				60134	5	6	1	35	20	30	15	
				60135	6	7	1	65	23	34	15	
				60136	7	8	1	5	27	31	15	
				60137	8	9	1	5	17	6	15	
				60138	9	10	1	20	16	12	10	
				60139	10	11	1	50	19	20	10	
				60140	11	12	1	125	22	34	40	
				60141	12	13	1	30	13	9	15	
				60142	13	14.5	1.5	15	10	42	15	
				60143	14.5	16	1.5	15	12	160	10	
				60144	16	17.5	1.5	20	14	12	10	
				60145	17.5	19	1.5	15	8	86	15	
				60146	19	20.5	1.5	105	71	16	15	
				60147	20.5	22	1.5	5	13	4	15	
				60148	22	23.5	1.5	5	12	7	10	
				60149	23.5	25	1.5	385	63	41	25	
				60150	25	26.5	1.5	5	20	12	10	
				60151	26.5	28	1.5	30	22	5	15	
				60152	28	29.5	1.5	10	25	15	15	
					29.5	31	1.5	30	35	43	15	
				60154	31	32.5	1.5	140	28	20	15	
				60155	32.5	34	1.5	180	27	96	10	
				60156	34	35.5	1.5	6121	62	39	25	
				60157	35.5	37	1.5	150	17	15	20	
				60158	37	38.5	1.5	30	9	16	20	
				60159	38.5	40	1.5	10	8	93	10	
				60160	40	41.5	1.5	5	8	98	10	
				60161	41.5	43	1.5	10	6	75	5	
				60162	43	44.5	1.5	5	7	29	10	
				60163	44.5	46	1.5	15	7	176	5	
				60164	46	47.5	1.5	5	8	127	10	
				60165	47.5	49	1.5	10	8	45	10	
				60166	49	50.5	1.5	5	8	37	5	
88.8	118.42	Homblende Feldspar Breccia		Strong quartz/calcite veins approx. 7%. Brecciated, mottled, foliated. Medium grained, green. Fractures 45 deg., veins 45 deg., frs = 5/m, vns = 5/m.	60167	50.5	52	1.5	5	8	50	5
				60168	52	53.5	1.5	225	14	102	15	
				60169	53.5	55	1.5	10	5	22	5	
				60170	55	56.5	1.5	5	7	26	15	
				60171	56.5	58	1.5	10	7	34	40	
				60172	58	59.5	1.5	10	21	73	10	
				60173	59.5	61	1.5	5	12	57	10	
				60174	61	62.5	1.5	5	10	143	20	
				60175	62.5	64	1.5	5	9	143	15	
				60176	64	65.5	1.5	5	9	16	5	
				60177	65.5	67	1.5	5	7	7	10	
				60178	67	68.5	1.5	5	9	5	5	
				60179	68.5	70	1.5	10	45	60	30	
				60180	70	71.5	1.5	980	11	344	10	
				60181	71.5	73	1.5	180	11	248	10	
				60182	73	74.5	1.5	15	21	47	20	
				60183	74.5	76	1.5	205	70	60	65	
				60184	76	77.5	1.5	35	14	25	10	
				60185	77.5	79	1.5	55	31	65	10	
				60186	79	80.5	1.5	80	75	319	75	
118.42	135.05	Homblende Feldspar Breccia		H - 1 zone. Variable zone of intense black chlorite plus minor sulphide, k-feldspar alteration and intensely brecciated rock with strong pyrite mineralization. Local pyrite veins up to 4 cm, local wispy arsenopyrite. Mottled, fragmental, veined. Medium grained, green. Veins 45 deg., fracture 50 deg., frs = 5/m, vns = 6/m.	60187	80.5	82	1.5	140	35	182	35

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample	Sample	Interval	Assay / Geochem				
From	To			No.	From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
				60188	82	83.5	1.5	125	21	103	10
			Moderate patchy silica	60189	83.5	85	1.5	15	15	41	10
			Strong pervasive chlorite	60190	85	86.5	1.5	506	24	113	35
			Strong pervasive carbonate	60191	86.5	88	1.5	710	82	89	110
			Moderate patchy sericite	60192	88	89.5	1.5	75	47	119	55
			Strong pervasive k-spar	60193	89.5	91	1.5	100	11	53	15
			Weak patchy hematite	60194	91	92.5	1.5	15	12	35	30
			Intense vein pyrite	60195	92.5	94	1.5	10	10	48	25
			Quartz calcite microveins	60196	94	95.5	1.5	30	13	75	20
			118.42 to 118.45 m - pyrite vein	60197	95.5	97	1.5	10	7	20	10
			119.1 to 119.35 m - minor hematite, arsenopyrite and pyrite in quartz/calcite/	60198	97	98.5	1.5	10	8	28	20
			chlorite vein	60199	98.5	100	1.5	5	8	35	10
			119.35 to 120.1 m - intense black chlorite with fine pyrite crystals	60200	100	101.5	1.5	15	10	30	15
			From 120.1 to 131.06 m - zone of abundant chlorite, minor pyrite patches an	60201	101.5	103	1.5	5	10	32	10
			veinlets. Local sericite altered fragments	60202	103	104.5	1.5	5	10	43	10
			125.75 to 125.80 m - calcite vein	60203	104.5	106	1.5	190	22	171	70
			131.06 to 135.05 m - zone of k-feldspar altered fragments, as well as pyrite	60204	106	107.5	1.5	10	12	30	60
			rich fragments in chloritic, sericitic minor pyrite rich matrix. Pyrite approx.	60205	107.5	109	1.5	10	11	30	40
			10-15% overall.	60206	109	110	1	15	13	40	30
				60207	110	111	1	5	14	37	20
135.05	143.26	Homblende Feldspar Breccia	Strong calcite/quartz veining, locally crenulated. Foliated, fragmental, veined	60208	111	112	1	20	16	94	20
			Medium grained, dark gray. Foliation 45 deg., veins 45 deg., frs = 3/m,	60209	112	113	1	15	13	69	45
			vns = 5/m.	60210	113	114	1	5	11	36	25
			Moderate patchy silica	60211	114	115	1	15	17	78	35
			Moderate pervasive chlorite	60212	115	116	1	5	10	42	20
			Moderate pervasive sericite	60213	116	117	1	15	9	99	20
			Moderate pervasive k-spar	60214	117	118	1	10	12	172	45
			Moderate disseminated pyrite	60215	118	118.42	0.42	35	12	121	25
			Strong quartz calcite microveins	60216	118.42	119.75	1.33	0.075	65	535	935
				60217	119.75	120.5	0.75	20	34	195	30
			E.O.H. 143.26 m	60218	120.5	121.5	1.5	40	39	183	40
				60219	121.5	122.5	1.5	15	30	178	30
				60220	122.5	123.5	1.5	25	37	135	25
				60221	123.5	125	1.5	40	31	145	30
				60222	125	126	1	20	30	145	25
				60223	126	127	1	10	30	150	40
				60224	127	128	1	30	36	161	30
				60225	128	129	1	35	34	141	35
				60226	129	130	1	15	34	133	45
				60227	130	131	1	25	27	151	50
				60228	131	132	1	30	27	102	60
				60229	132	133	1	20	26	148	80
				60230	133	134	1	35	36	152	110
				60231	134	135	1	40	32	154	105
				60232	135	138	1	35	29	68	75
				60233	138	137.5	1.5	10	19	82	80
				60234	137.5	139	1.5	20	25	86	150
				60235	139	140.5	1.5	15	28	98	100
				60236	140.5	142	1.5	30	29	116	70
				60237	142	143.26	1.26	25	22	122	85

TEUTON RESOURCES CORPORATION LTD.

PROPERTY: Clone Property					HOLE No. DDH-CI-97-133						
Azimuth: 160 degrees		Dip: -45 degree		Depth: 114.3 m		Date:		Logged by: ERK			
Meterage From To	Rock Type	Alteration, Mineralization & Structure Description	Sample No.	Sample Interval		Assay / Geochem					
				From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)	
			60238	1.21	2	0.79	25	12	115	20	
1.21	87.5	Hornblende Feldspar Breccia	Mottled, red/green, local epidote associated with quartz veins. Local quartz/calcite/chlorite veinlets up to 5 mm. Local intense k-feldspar alteration. Wis veined, hematite stockwork. Medium grained, red. Veins 45 deg., fractures 45 deg., frs = 4/m, vms = 12/m.	60239	2	3	1	25	12	23	15
			60240	3	4	1	10	9	12	20	
			60241	4	5	1	190	29	31	15	
			60242	5	6	1	95	23	48	15	
			60243	6	7	1	20	14	12	10	
			60244	7	8	1	5	12	193	5	
			60245	8	9	1	5	15	7	15	
			60246	9	10	1	5	17	14	15	
			60247	10	11	1	5	15	18	10	
			60248	11	12	1	5	14	24	5	
			60249	12	13	1	5	15	16	15	
			60250	13	14	1	115	18	12	20	
			60251	14	15.5	1.5	235	19	37	15	
			60252	15.5	17	1.5	20	17	87	15	
			60253	17	18.5	1.5	5	11	29	15	
			60254	18.5	20	1.5	500	77	116	25	
			60255	20	21.5	1.5	110	24	12	10	
			60256	21.5	23	1.5	45	17	47	5	
			60257	23	24.5	1.5	40	18	72	10	
			60258	24.5	26	1.5	45	17	14	10	
			60259	26	27.5	1.5	75	74	11	10	
			60260	27.5	29	1.5	50	9	28	10	
			60261	29	30.5	1.5	40	8	8	10	
			60262	30.5	32	1.5	45	8	93	10	
			60263	32	33.5	1.5	30	9	13	10	
			60264	33.5	35	1.5	70	7	43	10	
			60265	35	36.5	1.5	50	11	6	20	
			60266	36.5	38	1.5	55	15	15	15	
			60267	38	39.5	1.5	20	7	15	5	
			60268	39.5	41	1.5	20	7	30	10	
			60269	41	42.5	1.5	35	7	88	5	
			60270	42.5	44	1.5	15	6	50	5	
			60271	44	45.5	1.5	65	17	74	10	
87.48	91	Hornblende Feldspar Breccia	H - 1 zone. Generally, weak zone of sulfide mineralization in intensely chlorit altered zone. Pyrite approx. 5% with 1-2% arsenopyrite, minor hematite and traces chalcopyrite. Foliated, mottled. Medium grained, dark green. Veins 60 deg., foliation 30 deg., frs = 3/m, vms = 10/m.	60272	45.5	47	1.5	30	11	28	10
			Moderate patchy silica	60273	47	48.5	1.5	25	7	24	5
			Strong pervasive chlorite	60274	48.5	50	1.5	5	9	30	10
			Weak pervasive carbonate	60275	50	51.5	1.5	15	8	77	15
			Weak patchy magnetite	60276	51.5	53	1.5	35	12	47	10
			Moderate pervasive k-spar	60277	53	54.5	1.5	20	20	100	5
			Weak patchy hematite	60278	54.5	56	1.5	45	10	184	10
			Strong vein pyrite	60279	56	57.5	1.5	25	11	47	75
			Quartz calcite microveins	60280	57.5	59	1.5	35	12	33	15
				60281	59	60.5	1.5	35	7	17	15
				60282	60.5	62	1.5	15	7	12	10
				60283	62	63.5	1.5	10	6	63	15
				60284	63.5	65	1.5	20	5	73	5
				60285	65	66.5	1.5	15	11	25	5
				60286	66.5	68	1.5	40	11	79	15
				60287	68	69.5	1.5	235	27	82	15
				60288	69.5	71	1.5	685	23	142	15
91	115	Hornblende Feldspar Breccia	Generally, strong quartz/calcite stockwork approx. 10% of section. Minor narrow pyrite veinlets, local black chlorite patches and local intense k-feldspar alteration. Minor limonite on fractures. Foliated, mottled, veined. Medium grained, light green. Veins 60 deg., foliation 45 deg., frs = 3/m, vms = 15/m.	60289	71	72	1	0.16	15	994	10
			Moderate patchy silica	60290	72	73.5	1.5	35	11	160	5
				60291	73.5	75	1.5	10	12	19	15
				60292	75	76.5	1.5	55	7	25	10
				60293	76.5	78	1.5	15	6	40	5
				60294	78	79.5	1.5	20	16	37	10

TEUTON RESOURCES CORPORATION LTD.

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample No.	Sample Interval		Assay / Geochem				
From	To				From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
				60238	1.21	2	0.79	25	12	115	20
			Moderate pervasive carbonate	60295	78.5	81	1.5	110	23	61	15
			Moderate pervasive k-spar	60296	81	82.5	1.5	235	19	42	20
			Moderate disseminated pyrite	60297	82.5	84	1.5	590	42	119	30
			Strong quartz calcite microveins	60298	84	85.5	1.5	8,036	65	262	70
				60299	85.5	86.5	1	380	61	355	60
			102.5 to 102.54 m - pyrite veinlet	60300	86.5	87.5	1	8,042	236	393	300
			102.8 to 103.3 m - intense k-feldspar alteration to a white rock with wispy chlorite	60301	87.5	88.5	1	8,106	466	1034	720
				60302	88.5	89.5	1	255	114	252	170
				60303	89.5	90.63	1.13	8,033	447	1170	2200
115	117.5	Homblende Feldspar Breccia	Zone of sulfide in intense black chlorite alteration. Foliated, veined. Medium grained, dark gray. Veins 70 deg., foliation 60 deg., frs = 3/m, vns = 15/m.	60304	90.63	91.5	0.87	25	11	32	75
			Weak patchy silica	60305	91.5	92.5	1	5	16	59	95
			Intense pervasive chlorite	60306	92.5	93.5	1	5	19	35	50
			Weak pervasive carbonate	60307	93.5	95	1.5	5	22	80	40
			Weak patchy sericite	60308	95	96.5	1.5	35	13	95	30
			Weak patchy magnetite	60309	96.5	98	1.5	170	17	116	45
			Weak pervasive k-spar	60310	98	99.5	1.5	130	12	90	60
			Weak patchy hematite	60311	99.5	101	1.5	140	27	127	185
			Strong vein pyrite	60312	101	102.5	1.5	820	25	372	990
			Quartz calcite microveins	60313	102.5	103.5	1.5	20	12	47	100
				60314	103.5	105	1.5	5	11	28	45
				60315	105	108.5	1.5	35	12	21	50
			115.05 to 115.65 m - semi-massive sulfide (coarse pyrite veins up to 10 cm with minor arsenopyrite and traces chalcopyrite).	60316	108.5	108	1.5	40	10	12	30
				60317	108	109.5	1.5	40	10	8	15
				60318	109.5	111	1.5	20	11	28	16
117.5	128.02	Homblende Feldspar Breccia	Local chlorite patches, local intense sericite alteration. Foliated, mottled, veined. Medium grained, light gray. Veins 60 deg., fractures 60 deg., frs = 5/m, vns = 10/m.	60319	111	112.5	1.5	55	10	37	25
			Weak patchy silica	60320	112.5	114	1.5	15	11	23	30
			Moderate pervasive chlorite	60321	114	114.9	0.9	930	117	809	1130
			Moderate pervasive sericite	60322	114.9	116	1.1	20	27	101	30
			Moderate pervasive k-spar	60323	116	117	1	20	32	102	35
			Moderate disseminated pyrite	60324	117	118	1	5	31	91	15
			Quartz calcite microveins	60325	118	119	1	30	35	115	25
				60326	119	120	1	5	33	85	20
				60327	120	122	2	10	35	87	25
				60328	122	124	2	15	33	121	25
			120.5 to 120.6 m - calcite/quartz vein	60329	124	125.5	1.5	30	33	151	20
				60330	125.5	127	1.5	10	33	152	20
			E.O.H. 128.02 m	60331	127	128.02	1.02	60	29	93	25

PROPERTY:		Clone Property			HOLE No.		DDH-CI-97-134						
Azimuth:		185 degrees		Dip: -60 degree		Depth:173.74 m		Date:		Logged by:			
Meterage		Rock Type		Alteration, Mineralization		Sample		Interval		Assay / Geochem			
From	To			& Structure Description		No.	From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
1.22	37.7	Hornblende Feldspar Breccia		Variably green/red mottled with strong hematite stockwork at 1.22 m. At 13 m local intense k-feldspar alteration to a pink/purple color. From 13 m downhole, definite decrease in hematite content. Mottled, veined, hematite stockwork. Medium grained, red. Veins 30 deg. Fractures 45 deg. frs=6/m vns=15/m		60332	1.22	2	0.78	60	19	791	20
				Moderate patchy silica		60337	6	7	1	20	35	47	30
				Moderate pervasive chlorite		60338	7	8.5	1.5	10	35	58	30
				Moderate pervasive carbonate		60339	8.5	10	1.5	5	38	89	30
				Moderate pervasive k-spar		60340	10	11.5	1.5	55	43	212	30
				Strong hematite stockwork		60341	11.5	13	1.5	60	31	104	25
				Weak disseminated pyrite		60342	13	14.5	1.5	20	37	167	25
				Quartz/calcite microveins		60343	14.5	16	1.5	65	32	139	15
				60344		60344	16	17.5	1.5	30	34	127	25
				1.22 to 13 m, H-1 Zone Generally weak zone of chlorite, hematite and k-feldspar alteration		60345	17.5	19	1.5	15	33	139	20
				60346		60346	19	20.5	1.5	20	37	109	20
				3.7 - 4 m strong dark green chlorite with blood red hematite patches approx 10 - 15 %		60347	20.5	22	1.5	30	27	87	20
				60348		60348	22	23.5	1.5	20	27	89	20
				11 - 11.98 m Strong pink carbonate veining approx. 30 - 40 %		60349	23.5	25	1.5	30	26	89	25
				60350		60350	25	26.5	1.5	15	41	146	35
				16 - 23.2 m Strong local quartz/calcite/epidote veining as narrow 1 - 5 mm stringers at 20.4 m.		60351	26.5	28	1.5	10	37	89	20
				20.4 - 20.45 m Quartz/epidote stringers		60352	28	29.5	1.5	40	29	97	35
				32.1 - 34.2 m Strong k-feldspar alteration with moderately strong wispy hematite stockwork approx. 15 %		60353	29.5	31	1.5	20	40	75	20
				60354		60354	31	32.5	1.5	35	28	131	30
				34.2 - 34.4 m Brecciated rock with approx. 50 % calcite cementing zone.		60355	32.5	34	1.5	65	35	348	20
				36.2 - 36.25 m Pink calcite/quartz vein.		60356	34	35.5	1.5	45	33	190	25
				37.9 m Patchy pyrite approx. 5 %.		60357	35.5	36.5	1	100	20	122	10
				60358		60358	36.5	37.89	1.39	195	23	175	20
37.7	56.81	Hornblende Feldspar Breccia		Strong local quartz/calcite stockwork up to 15 %. Local intense K-feldspar. Foliated, mottled. Medium grained, dark green. Veins 20 deg. Fractures 45 deg. Frs=6/m vns=6/m		60359	37.84	39	1.11	90	51	155	205
				Moderate patchy silica		60362	42	43.5	1.5	55	38	255	140
				Moderate pervasive chlorite		60363	43.5	45	1.5	25	40	275	90
				Weak pervasive carbonate		60364	45	46.5	1.5	60	34	217	75
				Moderate pervasive k-spar		60365	46.5	48	1.5	75	40	131	95
				Moderate disseminated pyrite		60366	48	49.5	1.5	50	37	151	65
				Quartz/calcite microveins		60367	49.5	51	1.5	20	50	150	100
				60368		60368	51	52.5	1.5	25	35	121	105
				37.9 - 38.4 m strong pyrite veinlets and patches approx. 10 %.		60369	52.5	54	1.5	415	48	393	115
				42.2 - 43 m broken core.		60370	54	55.5	1.5	180	48	267	135
				45.3 - 47 m Strong quartz/epidote veins up to 12 cm approx. 10 %.		60371	55.5	56.87	1.37	410	268	453	380
				53.6 - 54 m Quartz/calcite/epidote vein at 45 deg. to C.A. with wispy hematite minor pyrite.		60372	56.87	58	1.13	6374	686	3208	980
				60373		60373	58	59	1	140	48	173	75
				56.5 - 56.55 m Narrow quartz/calcite/chlorite veinlets.		60374	59	60	1	75	27	152	50
				60375		60375	60	61	1	255	32	191	230
56.87	57.92	Semi Massive Hematite Vein		Massive hematite/chlorite/pyrite stringers. Veined. Medium grained, dark red. Veins 45 deg. fractures 45 deg. Frs=5/m Vns=10/m		60376	61	62.5	1.5	75	13	155	85
				Weak patchy silica		60377	62.5	64	1.5	55	18	390	100
				Strong pervasive chlorite		60378	64	65.5	1.5	5	18	340	70
				Moderate pervasive carbonate		60379	65.5	67	1.5	55	13	77	25
				Strong patchy magnetite		60380	67	68.5	1.5	45	13	376	25
				Moderate pervasive k-spar		60382	70	71.5	1.5	55	12	108	45
				Intense vein hematite		60383	71.5	73	1.5	30	11	79	25
				Intense vein pyrite		60384	73	74.5	1.5	15	11	76	15
				Quartz/calcite microveins		60385	74.5	76	1.5	5	13	83	20
				60386		60386	76	77.5	1.5	45	14	88	20
				56.87 - 57.25 m Abundant magnetite approx. 30 %.		60387	77.5	79	1.5	15	14	115	50

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample	Sample	Interval	Width	Assay / Geochem				
From	To			No.	From	To		Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)	
			57.25 - 57.92 m Coarse pyrite stringers up to 2 cm approx. 15 %, minor coarse patches of chalcopyrite.	60388	79	80.5	1.5	30	14	90	40	
				60389	80.5	82	1.5	35	14	95	15	
				60390	82	83.5	1.5	35	14	108	20	
57.92	121.95	Homblende Feldspar Crystalline	Strong quartz/calcite stockwork approx. 7 - 8 % of rock. Crystalline. Medium grained, dark gray. Veins 60 deg. Fractures 60 deg. Fr=3/m Vn=3/m	60391	83.5	85	1.5	20	15	122	30	
			Moderate patchy silica	60392	85	86.5	1.5	10	16	178	10	
			Moderate pervasive chlorite	60393	86.5	88	1.5	5	14	131	15	
			Moderate pervasive carbonate	60394	88	89.5	1.5	50	13	100	15	
			Moderate pervasive k-spar	60395	89.5	91	1.5	15	14	97	15	
			Moderate disseminated pyrite	60396	91	92.5	1.5	10	12	103	25	
			Strong quartz/calcite microveins	60397	92.5	94	1.5	10	10	36	45	
				60398	94	95.5	1.5	30	15	76	50	
				60399	95.5	97	1.5	40	17	134	70	
				71.93 - 73.3 m Broken core, limonitic on fractures.	60400	97	98.5	1.5	30	14	138	25
				77.9 - 80 m Broken core, highly brecciated with strong pink calcite veinlets, minor gouge, vuggy, limonitic on fractures.	60401	98.5	100	1.5	30	13	99	30
				82.2 m Pink calcite vein (2 cm)	60402	100	101.5	1.5	35	13	98	35
				95.8 - 96.2 m Mosaic breccia, strong black chlorite between fragments that are up to 2 cm.	60403	101.5	103	1.5	60	17	94	60
				96.4 - 96.5 m Pink calcite/quartz/chlorite vein.	60404	103	104.5	1.5	10	13	76	30
				From 99 m down hole, increase in f-feldspar alteration with associated increase in black chlorite veinlets.	60405	104.5	106	1.5	60	14	128	95
				99.85 - 99.9 m Patchy pyrite with intense k-feldspar alteration.	60406	106	107.5	1.5	36	14	81	20
			at 104.95 m 5 mm patchy pyrite veinlet.	60407	107.5	109	1.5	165	12	127	70	
			at 105.2 K-feldspar/silicified zone approx. 10 cm with wispy pyrite and black chlorite.	60408	109	110.5	1.5	45	14	99	20	
			107.2 - 108 m K-feldspar zone with minor hematite plus wispy pyrite approx. 1-2 mm wide.	60409	110.5	112	1.5	15	13	93	5	
			117.5 - 118.6 m Broken core, limonitic, minor gouge.	60410	112	113.5	1.5	55	11	111	15	
			120.5 - 121.2 m Mosaic texture with black chlorite.	60411	113.5	115	1.5	30	15	142	15	
				60412	115	116.5	1.5	70	15	184	30	
				60413	116.5	118	1.5	50	16	194	55	
				60414	118	119.5	1.5	110	14	139	35	
				60415	119.5	121	1.5	95	12	112	20	
				60416	121	122	1	60	14	131	25	
				60417	122	122.82	0.82	180	27	132	70	
121.95	124.46	Semi Massive Sulfide	S-Zone. Strong quartz/calcite veining with black chlorite and massive to semi massive pyrite/minor arsenopyrite stringers plus vein sulfide approx. 10 %	60418	122.82	123.5	0.68	925	60	1060	175	
			Veined, wispy, foliated. Medium grained, light black. Veins 45 deg. Fractures 45 deg. Fr=10/m Vn=20/m	60419	123.5	124.42	0.98	100	20	150	40	
			Moderate patchy silica	60420	124.42	126	1.58	95	35	109	80	
			Strong pervasive chlorite	60421	126	127.5	1.5	35	30	66	35	
			Weak pervasive carbonate	60422	127.5	129	1.5	35	27	73	30	
			Weak pervasive k-spar	60423	129	130.5	1.5	55	26	134	15	
			Intense vein pyrite	60424	130.5	132	1.5	40	23	108	25	
			quartz/calcite microveins	60425	132	133.5	1.5	45	25	170	15	
				60426	133.5	135	1.5	165	52	193	655	
				60427	135	136.5	1.5	90	23	60	430	
				60428	136.5	138	1.5	500	55	158	180	
				122.2 - 122.7 m Approx. 50 % quartz/calcite with stringers of sulfide in chloritic rich rock.	60429	138	139.5	1.5	155	77	118	2745
				122.9 - 122.95 m Pyrite vein.	60430	139.5	141	1.5	0.041	83	229	5405
				123.3 - 123.5 m Approx. 50 % pyrite/arsenopyrite.	431	141	142.5	1.5	385	45	440	985
					60432	142.5	144	1.5	125	25	161	445
					60433	144	145.5	1.5	75	18	241	135
124.46	173.74	Homblende Feldspar Breccia	Foliated, wispy. Medium grained, light green. Veins 45 deg. foliation 45 deg. Fr=6/m Vn=7/m	60434	145.5	147	1.5	45	14	171	110	
			Moderate patchy silica	60435	147	148.5	1.5	50	22	178	390	
			Moderate pervasive chlorite	60436	148.5	150	1.5	55	18	210	75	
			Moderate pervasive carbonate	60437	150	151.5	1.5	115	13	136	95	
			Weak patchy sericite	60438	151.5	153	1.5	435	54	99	760	
			Moderate pervasive k-spar	60439	153	154.5	1.5	70	15	108	120	
			Moderate disseminated pyrite	60440	154.5	156	1.5	410	89	125	2510	
			Quartz/calcite microveins	60441	156	157.5	1.5	95	13	44	180	
				60442	157.5	158	1.5	50	14	37	50	
				60443	158	160.5	1.5	285	18	38	65	
				From 124.42 - 130 m, highly chloritic with local fine patchy pyrite approx 3 - 4 %.	60444	160.5	162	1.5	85	24	61	185
				Local intense quartz/calcite veining at 126.8 - 130 m approx. 15 %	60445	162	163.5	1.5	675	20	92	335
				Local intense k-feldspar alteration with pyrite/arsenopyrite. Local fine disseminated arsenopyrite.	60446	163.5	165	1.5	40	17	50	75
				128.8 - 129 m up to 50 % quartz/calcite.	60447	165	166.5	1.5	30	39	220	40
					60448	166.5	168	1.5	40	15	85	30

TEUTON RESOURCES CORPORATION LTD.

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample	Sample	Interval	Width	Assay / Geochem			
From	To			No.	From	To		Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
			131.2 - 132 m Up to 50 % quartz/calcite.	60449	168	169.5	1.5	55	25	116	85
			134.1 - 135 m Wispy pyrite/arsenopyrite.	60450	169.5	171	1.5	50	17	91	40
			From 138- 149.2 m Local highly k-feldspar altered with wispy pyrite/arsenopyrite and traces chalcopyrite. Sulfides approx. 5 - 7 %.	60451	171	172.5	1.5	30	16	71	30
			Pyrite and arsenopyrite also occur as fine disseminated grains. Rock has been altered to a light green color.	60452	172.5	173.74	1.24	65	13	60	35
			151 - 153.5 m Calcite vein. Up to 40 % calcite/quartz as core is along a vein up to 4 cm wide. Vein is vuggy and barren.								
			Arsenopyrite appears to end at 155.45 m.								
			From 154.5 - 156.8 m Highly k-feldspar altered with approx. 15 % quartz/calcite stockwork. Minor wispy pyrite veinlets associated with blebs of arsenopyrite. Carbonate veinlets up to 1 cm wide at 70 deg. to C.A.								
			K-feldspar alteration becomes weaker at 157 m.								
			164.1 - 164.15 m Calcite vein.								
			165.05 - 165.7 m calcite vein.								
			170.2 - 173.74 m Intense k-feldspar alteration, minor quartz/calcite veinlets, wispy pyrite approx. 2 %, traces arsenopyrite								
			E. O. H. 173.74 m								

TEUTON RESOURCES CORPORATION LTD.

PROPERTY: Clone Property				HOLE No.		DDH-CI-97-135					
Azimuth: 185 degrees		Dip: -55 degree		Depth: 161.39 m		Date:		Logged by: ERK			
Meterage		Rock Type		Alteration, Mineralization		Sample		Assay / Geochem			
From	To	& Structure Description		No.	From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
				60453	0.91	3	2.08	35	8	34	10
0.91	15.84	Hornblende Feldspar breccia	Mottled red/green, strong quartz/calcite microveinlets, local intense k-feldspar alteration. Mottled, veined, hematite stockwork, medium grained, light red.	60454	3	4.5	1.5	55	12	47	15
			fractures 45 deg. veins 70 deg. Frs=6/m Vns=8/m	60455	4.5	6	1.05	45	22	29	10
			Moderate patchy silica	60456	6	7.5	1.5	25	20	23	10
			Moderate pervasive chlorite	60457	7.5	9	1.5	95	20	331	20
			Moderate pervasive carbonate	60458	9	10.5	1.5	55	14	13	10
			Moderate pervasive k-spar	60459	10.5	12	1.5	98	12	10	10
			Strong hematite stockwork	60460	12	13.5	1.5	85	15	10	10
			weak disseminated pyrite	60481	13.5	15	1.5	70	14	9	10
			Strong quartz/calcite microveins	60482	15	15.84	0.84	0.047	16	80	15
				60463	15.84	16.37	0.53	1,374	26	426	100
				60464	16.37	17	0.63	265	41	2495	70
15.84	24.75	Semi Massive Hematite	H-1 Zone. Zone of massive to semi massive hematite stringers and veins, black chlorite, strong chalcopryrite mineralization as fracture fillings and disseminations, strong magnetite and visible gold in 3 separate localities.	60485	17	18	1	215	87	9132	80
			Veined. Medium grained, light red. Veins 45 deg. Veins 15 deg.	60466	18	19	1	120	115	1144	100
			Frs=6/m Vns=20/m	60467	19	20	1	985	70	1093	150
			Intense pervasive chlorite	60468	20	21	1	0.078	132	2184	175
			Weak pervasive carbonate	60469	21	22	1	385	162	2793	215
			Strong patchy magnetite	60470	22	23.3	1.3	0.136	124	1436	180
			Intense vein hematite	60471	23.3	24.75	1.45	200	71	656	35
			Quartz/calcite microveins	60472	24.75	26	1.25	100	79	308	40
				60473	26	27.5	1.75	40	41	190	30
				60474	27.5	29	1.5	75	41	223	30
				60475	29	30.5	1.5	140	40	329	35
			15.84 - 16.37 m Semi massive hematite. Strong black chlorite, hematite approx. 50%. Visible gold at 16.05 and 16.3 m.	60476	30.5	32	1.5	25	48	258	30
			From 16.37 - 19.4 m Strong hematite stockwork.	60477	32	33.5	1.5	20	36	97	15
			19.4 - 19.8 m Massive hematite. Strong chalcopryrite mineralization.	60478	33.5	35	1.5	140	48	114	25
			20.1 - 21.9 Massive hematite/visible gold at 20.2 m, strong patchy magnetite at 21 - 29 m.	60479	35	36.5	1.5	15	42	101	20
				60480	36.5	38	1.5	35	40	143	30
				60481	38	39.5	1.5	75	38	128	40
			22.1 - 23.1 m Semi massive hematite. Strong k-feldspar alteration with massive hematite at 22.1 - 22.6 m. From 23.1 - 24.56 m hematite stringers approx. 10% of zone.	60482	39.5	41	1.5	25	37	81	40
				60483	41	42	1	55	32	60	35
				60484	42	42.71	0.71	20	27	121	30
				60485	42.71	43.5	0.79	40	56	336	85
24.75	42.71	Hornblende Feldspar Breccia	Strong wispy hematite stockwork, strong quartz/calcite microveinlets, local minor quartz/epidote veinlets. Local intense k-feldspar alteration over 30 cm lengths.	60486	43.5	44.4	0.9	0.356	983	986	990
			Mottled, stockwork, veined, wispy. Medium grained, light red.	60487	44.4	45	0.6	35	82	131	50
			Veined 35 deg. Fractures 45 deg. Frs=5/m Vns=10/m	60488	45	46.5	1.5	5	37	142	35
			Weak patchy silica	60489	46.5	48	1.5	15	37	128	45
			Moderate pervasive chlorite	60490	48	49.5	1.5	130	58	212	80
			Moderate pervasive carbonate	60491	49.5	51	1.5	0.038	265	845	1370
				60492	51	52.5	1.5	0.042	187	199	950
				60493	52.5	54	1.5	355	44	129	70
				60494	54	55.5	1.5	775	61	362	80
				60495	55.5	57	1.5	255	35	119	65
				60496	57	58.5	1.5	20	24	70	45
				60497	58.5	60	1.5	115	24	103	50
				60498	60	61.5	1.5	20	41	177	55
42.71	44.4	Semi Massive Hematite	H Zone. (S-2a ?) Abundant black chlorite, hematite veinlets and stringers. Intense k-feldspar alteration, minor chalcopryrite, traces malachite. 15 cm in middle with quartz/calcite/chlorite veinlets	60499	61.5	63	1.5	15	37	157	50
			Veined, mottled. Medium grained, dark red. Veins 45 deg. Fractures 60 deg. Frs=6/m vns=15/m	60500	63	64.5	1.5	275	42	383	80
			Weak patchy silica	60501	64.5	66	1.5	30	36	162	65
				60502	66	67.5	1.5	10	36	237	40
				60503	67.5	69	1.5	25	33	219	65
				60504	69	70.5	1.5	35	35	228	50
				60505	70.5	72	1.5	10	25	142	40
				60506	72	73.5	1.5	120	43	285	55
				60507	73.5	75	1.5	75	54	284	65
				60508	75	76.5	1.5	120	20	116	20
				60509	76.5	78	1.5	50	24	164	130

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample No.	Sample From	Interval To	Width	Assay / Geochem			
From	To							Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
			Moderate quartz/calcite microveinlets	80453	0.91	3	2.08	35	8	34	10
				80510	78	79.5	1.5	440	73	351	1070
				60511	79.5	81	1.5	455	29	242	90
44.4	103.92	Hornblende Feldspar Breccia	Definite decrease in hematite content. Local intense k-feldspar alteration.	60512	81	82.5	1.5	55	21	167	40
			Mottled, veined. Medium grained, dark green. Veins 60 deg. Fractures 60 deg. Fr=6/m Vn=5/m.	60513	82.5	84	1.5	75	25	137	45
			Moderate patchy silica	60514	84	85.5	1.5	90	22	193	60
			Moderate pervasive chlorite	60515	85.5	87	1.5	365	23	228	90
			Moderate pervasive carbonate	60516	87	88.5	1.5	360	26	283	65
			Moderate pervasive k-spar	60517	88.5	90	1.5	25	15	109	30
			Weak patchy hematite	60518	90	91.5	1.5	35	16	64	35
			Moderate disseminated pyrite	60519	91.5	93	1.5	50	14	69	40
			Quartz/calcite microveins	60520	93	94.5	1.5	45	13	50	30
				60521	94.5	96	1.5	45	14	69	25
				60522	96	97.5	1.5	60	14	63	30
			At 46.6, 47.05, 47.1, 47.45, 47.95, 48.95-49.05 and 49.2 m, narrow pink quartz/calcite veinlets 1 - 2 cm wide.	60523	97.5	99	1.5	0.058	35	164	65
			48.95 - 50.9 m Intense K-feldspar alteration with black/green chlorite veins and patches from 1 - 4 cm wide.	60524	99	100	1	85	20	140	65
			52 - 56.5 m Intense k-feldspar alteration with strong chlorite.	60525	100	101	1	55	13	84	75
			54.9 - 55.06 m Wispy pyrite approx. 5 % in black chlorite veins.	60526	101	102	1	80	12	93	65
			From 56 - 56.5 m Fine 1 mm pyrite veinlets with black chlorite patches. Pyrite approx. 5 %.	60527	102	103	1	30	9	61	15
			60 - 62.5 m Patchy hematite rich calcite, coarse pyrite cubes approx. 7 %, strong chlorite.	60528	103	104	1	40	12	89	80
			63.7 - 64.5 m 50 % pink to white calcite/quartz/chlorite ss veins up to 10 mm	60529	104	105	1	0.036	1793	200	4.76
			From 67.45 - 73.5 m Local 2 - 3 cm pink calcite/quartz/chlorite veins approx. 5%	60530	105	106	1	0.012	1368	896	1.05
			77 - 103.42 m Strong k-feldspar alteration over zones up to 1 m in length. Wispy pyrite veinlets associated with alteration.	60531	106	107	1	0.083	192	385	905
			79.9 - 80 m Pyrite veinlets and patches approx. 20 %.	60532	107	108	1	50	30	97	190
			at 84.5 m, traces chalcopyrite in a highly k-feldspar altered section, minor patches of pyrite in section.	60533	108	109	1	45	23	98	65
			91.2 - 92.05 m Broken core, limonitic on fractures.	60534	109	110	1	135	36	117	130
			99 - 99.1 Pyrite vein	60535	110	111	1	50	38	213	85
				60536	111	112.5	1.5	560	89	230	860
				60537	112.5	114	1	0.083	194	211	2640
				60538	114	115.5	1.5	55	56	193	205
				60539	115.5	117	1.5	15	42	127	75
				60540	117	118.5	1.5	25	42	162	65
				60541	118.5	120	1	40	44	189	60
				60542	120	121.5	1.5	25	43	185	50
				60543	121.5	123	1.5	20	47	165	50
103.92	106	Semi Massive Sulfide	S-Zone. Strong arsenopyrite/pyrite veins, patches and grains in a highly k-feldspar altered rock.	60544	123	124.5	1.5	25	41	177	50
				60545	124.5	126	1.5	15	36	146	45
				60546	126	127.5	1.5	35	39	126	30
			104.2 - 104.7 Semi massive sulfide. Predominantly arsenopyrite approx. 50 % in highly k-feldspar altered mosaic textured breccia.	60547	127.5	128	1.5	55	36	116	35
			104.95 - 105.3 m Massive sulfide (predominantly pyrite).	60548	129	130.5	1.5	15	40	161	45
			105.2 - 105.25 m Massive sulfide (pyrite approx. 50 % with hematite).	60549	130.5	132	1.5	10	38	106	35
			105.8 - 105.95 m Massive sulfide (50 % arsenopyrite and pyrite in k-feldspar altered mosaic textured breccia).	60550	132	133.5	1.5	55	36	161	45
				60551	133.5	135	1.5	40	45	88	35
				60552	135	136.5	1.5	45	40	127	45
				60553	136.5	137.16	0.66	450	152	157	1540
106	161.54	Hornblende Feldspar Breccia	From 106 to 107 m, strong mosaic textured breccia. fragments up to 4 cm in chloritic matrix. Strong k-feldspar alteration veinlets up to 2 cm as selvage to chlorite veinlets approx. 1 - 2 mm. Mottled, foliated. Medium grained, dark green. Veins 30 deg. Fractures 45 deg. Fr=10/m Vn=6/m	60554	137.16	138	0.84	275	141	168	1330
			Moderate patchy silica	60555	138	139	1	30	43	99	85
			Moderate pervasive chlorite	60556	139	140	1	0.07	589	265	9675
			Weak pervasive carbonate	60557	140	141.5	1.5	20	40	100	60
			Weak patchy sericite	60558	141.5	142.5	1	45	37	149	50
			Moderate pervasive k-spar	60559	142.5	143.5	1	615	379	194	1605
			Moderate disseminated pyrite	60560	143.5	145	1.5	120	23	102	265
			Quartz/calcite microveinlets	60561	145	146.5	1.5	65	26	174	80
				60562	146.5	148	1.5	85	110	163	1850
				60563	148	149.5	1.5	40	38	174	45
				60564	149.5	151	1.5	15	21	92	15
				60565	151	152	1	50	36	238	30
			113.7 - 123 m Strong quartz/calcite microveinlet stockwork approx. 8 - 9 % as 2 - 5 mm wide veinlets.	60566	152	153	1	25	38	237	50
			128.7 - 133 m Local strong patchy epidote with zone at 132.7 to 133 m approx. 10 % epidote in quartz/calcite.	60567	153	154.5	1.5	40	39	271	80
				60568	154.5	156	1.5	10	41	144	65
				60569	156	157.5	1.5	0.033	520	164	750
			137.76 - 137.25 m Up to 50 % pyrite/minor arsenopyrite.	60570	157.5	159	1.5	60	32	145	115

TEUTON RESOURCES CORPORATION LTD.

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample	Sample	Interval	Width	Assay / Geochem			
From	To			No.	From	To		Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
			138.93 - 138.98 m Quartz/calcite/chlorite vein.	60453	0.91	3	2.08	35	8	34	10
			139.5 - 139.6 m Massive arsenopyrite/minor pyrite.	60671	159	160.5	1.5	70	48	137	115
			142.2 - 142.28 m Quartz/calcite vein								
			142.7 - 142.75 m Semi massive pyrite/minor arsenopyrite								
			143.5 - 145.5 m Strong k-feldspar alteration with wispy pyrite/ black chlorite veinlets.								
			From 145.5 - 158.5 m Strong chlorite with local wispy pyrite veinlets, pyrite approx. 6 % overall.								
			148.8 - 149 m Approx. 7 % quartz/calcite stockwork as veins up to 4 cm.								
			At 147.8 m, 2 cm semi massive pyrite vein.								
			150 - 153 m Wispy pyrite veinlets 1 - 2 mm wide approx. 7 %.								
			155.3 - 158.8 m Mosaic textured breccia, highly chloritic.								
			From 159 - 161.04 m Weakly sericitic, minor pyrite.								
			E. O. H. 161.04 m								

TEUTON RESOURCES CORPORATION LTD.

PROPERTY: Clone Property						HOLE No.		DDH-CI-87-136					
Azimuth:		185 degrees	Dip: -50 degree		Depth: 137.16 m	Date:				Logged by: ERK			
Meterage		Rock Type		Alteration, Mineralization		Sample		Assay / Geochem					
From	To			& Structure Description		No.	From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
1.21	13	Hornblende Feldspar Breccia		Mottled red/green with local intense k-feldspar. Local abundant epidote bleb		60573	1.21	3	1.79	5	10	47	10
				Mottled, veined, stockwork. Medium grained, light red. Veins 70 deg.		60574	3	4.5	1.5	5	9	31	10
				Fractures 60 deg. Frs=6/m Vns=20/m		60575	4.5	6	1.5	65	10	281	20
				Moderate patchy silica		60576	8	7.5	1.5	5	10	30	15
				Moderate pervasive chlorite		60577	7.5	9	1.5	35	10	24	15
				Moderate pervasive carbonate		60578	9	10.5	1.5	15	10	14	15
				Moderate pervasive k-spar		60579	10.5	12	1.5	20	11	188	20
				Strong stockwork hematite		60580	12	13	1	10	9	15	10
				Weak disseminated pyrite		60581	13	14	1	125	17	23	25
				Quartz/calcite microveinlets		60582	14	15	1	5	10	20	20
						60583	15	16	1	75	14	13	15
				8.08 - 8.24 m Semi massive hematite.		60584	16	17	1	55	92	242	35
						60585	17	18	1	5	51	252	35
13	20.05	Hornblende Feldspar Breccia		H-1 Zone. Weak zone consisting of intense black chlorite, strong k-feldspar		60586	18	19	1	5	39	142	35
				minor blood red hematite veinlets, narrow quartz/calcite/chlorite veinlets.		60587	19	20	1	5	45	148	60
				Mottled, veined. Medium grained, dark red. Veins 30 deg. Fractures 60 deg		60588	20	21.5	1.5	25	39	228	35
				Frs=5/m Vns=25/m		60589	21.5	23	1.5	10	45	141	40
				Weak patchy silica		60590	23	24	1	5	40	80	35
				Strong pervasive chlorite		60591	24	25	1	5	43	101	20
				Moderate pervasive carbonate		60592	25	26	1	220	95	729	120
				Strong pervasive k-spar		60593	26	27	1	50	39	211	60
				Strong stockwork hematite		60594	27	28.5	1.5	15	50	254	60
				Weak disseminated pyrite		60595	28.5	30	1.5	40	60	297	35
				Quartz/calcite microveinlets		60596	30	31.5	1.5	5	42	182	35
						60597	31.5	33	1.5	150	43	290	55
20.05	20.8	Hornblende Feldspar Breccia		Stockwork, mottled. Medium grained, dark red. Veins 45 deg. Fractures 60		60598	33	34.5	1.5	5	32	112	40
				deg. Frs=5/m Vns=15/m		60599	34.5	36	1.5	5	28	119	30
				Weak patchy silica		60600	36	37.12	1.12	5	32	502	45
				Moderate pervasive chlorite		61751	37.12	38	0.68	150	34	281	80
				Moderate pervasive carbonate		61752	38	39	1	510	74	338	108
				Moderate pervasive k-spar		61753	39	40	1	0.041	63	498	55
				Moderate stockwork hematite		61754	40	41	1	35	28	119	50
				Weak disseminated pyrite		61755	41	42.22	1.22	1000	276	118	400
				Quartz/calcite microveinlets		61756	42.22	43	0.78	430	289	758	400
						61757	43	44.5	1.5	5	43	162	60
20.8	23.5	Pyroxene Porphyry		Mottled with minor epidote microveinlets, variably chlorite altered, minor		61758	44.5	46	1.5	15	36	125	65
				hematite altered inclusions in the dyke. Porphyritic, brecciated.		61759	46	47.5	1.5	235	69	329	150
				Fine grained, dark green. Contact 70 deg. Veins 70 deg.		61760	47.5	49	1.5	25	32	312	100
				Frs=6/m Vns=5/m		61761	49	50.5	1.5	5	35	324	115
				Weak patchy silica		61762	50.5	52	1.5	50	31	156	155
				Moderate pervasive chlorite		61763	52	53.5	1.5	40	20	45	85
				Moderate pervasive carbonate		61764	53.5	55	1.5	10	18	56	40
				Weak pervasive k-spar		61765	55	56.5	1.5	30	31	200	85
				Weak patchy hematite		61766	56.5	58	1.5	85	48	280	85
				Weak disseminated pyrite		61767	58	59.5	1.5	75	32	123	80
				Quartz/calcite microveinlets		61768	59.5	61	1.5	30	23	127	65
						61769	61	62.5	1.5	35	22	152	75
23.5	29.5	Hornblende Feldspar Breccia		Local strong epidote/quartz/calcite veinlets, strong quartz/calcite microveinlet		61770	62.5	64	1.5	80	37	360	90
				approx. 50 %. Stockwork, brecciated. Medium grained, light red.		61771	64	65.5	1.5	30	28	197	60
				Veins 70 deg. Fractures 70 deg.		61772	65.5	67	1.5	40	34	180	75
				Frs=6/m Vns=15/m		61773	67	68.5	1.5	70	35	178	105
				Weak patchy silica		61774	68.5	70	1.5	65	35	177	105
				Moderate pervasive chlorite		61775	70	71.5	1.5	45	35	130	75
				Moderate pervasive carbonate		61776	71.5	73	1.5	200	27	245	80
				Moderate pervasive k-spar		61777	73	74.5	1.5	210	39	282	85
				Strong stockwork hematite		61778	74.5	76	1.5	30	30	347	90

TEUTON RESOURCES CORPORATION LTD.

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample	Sample	Interval	Width	Assay / Geochem			
From	To			No.	From			To	Au(ppb)	Co(ppm)	Cu(ppm)
			Weak disseminated pyrite	61779	76	77.5	1.5	5	42	266	80
			Strong quartz/calcite microveinlets	61780	77.5	79	1.5	55	34	278	100
				61781	79	80.5	1.5	25	25	138	45
			25.3 - 25.7 m H-1 Zone	61782	80.5	82	1.5	0.043	95	733	440
			Semi massive hematite zone with dark chlorite. Massive hematite at 25.6 -	61783	82	83.5	1.5	0.075	138	689	875
			25.7 m, strong chalcopyrite(chalcopyrite approx. 1 - 2 %.	61784	83.5	85	1.5	260	67	371	190
			Veined. Medium grained, dark red. Veins 70 deg. Fractures 45 deg.	61785	85	86.5	1.5	825	41	243	80
			Fr=4/m Vns=15/m	61786	86.5	88	1.5	5	37	145	115
			Weak patchy silica	61787	88	89.5	1.5	5	38	177	160
			Strong pervasive chlorite	61788	89.5	91	1.5	10	44	157	115
			Weak pervasive carbonate	61789	91	92.5	1.5	5	44	180	100
			Moderate pervasive k-spar	61790	92.5	94	1.5	20	39	134	125
			Strong stockwork hematite	61791	94	95.5	1.5	5	42	218	115
			Weak disseminated pyrite	61792	95.5	97	1.5	5	44	172	90
			Quartz/calcite microveinlets	61793	97	98.5	1.5	50	48	186	110
				61794	98.5	100	1.5	65	39	187	115
29.5	30.6	Pyroxene Porphyry	Post hematite stockwork dyke, strong epidote on fractures. Porphyritic,	61795	100	101.5	1.5	45	48	162	180
			brecciated. Medium grained dark green. Contact 20 deg. Fractures 20 deg.	61796	101.5	103	1.5	25	53	190	190
			Fr=6/m Vns=1/m	61797	103	104.5	1.5	50	43	144	165
			Moderate pervasive chlorite	61798	104.5	106	1.5	55	42	166	160
			Weak disseminated pyrite	61799	106	107.5	1.5	20	38	146	100
			Quartz/calcite microveinlets	61800	107.5	109	1.5	30	33	116	75
				61801	109	110.5	1.5	10	41	153	140
30.6	42.2	Hornblende Feldspar Breccia	Strong hematite alteration, local intense k-feldspar alteration. Mottled,	61802	110.5	112	1.5	40	39	178	110
			stockwork. Medium grained, dark red/green. Veins 45 deg. Fractures 45 de	61803	112	113	1	20	38	127	130
			Fr=6/m Vns=15/m	61804	113	113.93	0.93	0.204	1711	1344	1.88
			Moderate patchy silica	61805	113.93	114.6	0.67	165	78	173	575
			Moderate pervasive chlorite	61806	114.6	115.6	1	30	39	134	95
			Weak pervasive carbonate	61807	115.6	117	1.4	35	39	111	75
			Moderate pervasive k-spar	61808	117	118.5	1.5	55	40	210	120
			Strong stockwork hematite	61809	118.5	120	1.5	10	36	124	100
			Weak disseminated pyrite	61810	120	121.5	1.5	25	35	110	70
			Quartz/calcite microveinlets	61811	121.5	123	1.5	15	33	99	45
				61812	123	124.5	1.5	15	39	89	75
			31 - 31.9 m Strongly mottled light green	61813	124.5	126	1.5	10	41	145	80
			31.9 - 32.2 m Strong k-feldspar alteration to light red/pink rock.	61814	126	127.5	1.5	35	42	178	80
			32.7 - 32.78 m Hematite vein with epidote selvages.	61815	127.5	129	1.5	45	39	139	215
				61816	129	130.5	1.5	50	36	124	355
			37.12 - 42.22 m H-Zone.	61817	130.5	132	1.5	45	34	146	85
			Semi massive hematite. Strong zone of semi massive to massive hematite	61818	132	133.5	1.5	50	48	141	125
			veinlets in strongly chlorite altered rocks. Veined, stockwork, foliated.	61819	133.5	135	1.5	50	34	176	50
			Medium grained, dark red. Veins 45 deg. Fractures 45 deg.	61820	135	136.5	1.5	10	37	130	80
			Fr=5/m Vns=30/m	61821	136.5	137.16	1.5	5	35	118	80
			Moderate patchy silica								
			Strong pervasive chlorite								
			Weak pervasive carbonate								
			Moderate pervasive k-spar								
			Intense vein hematite								
			Weak disseminated pyrite								
			Quartz/calcite microveinlets								
			37.12 - 37.6 m Massive hematite, traces visible gold								
			38 - 38.2 m Massive hematite								
			38.2 - 41.6 m Strong hematite alteration								
			41.6 - 42.22 m Intense k-feldspar alteration to a pink/ light purple rock with								
			hematite/black chlorite stringers.								
			At 41.92 m Visible gold ?								
42.22	46.7	Hornblende Feldspar Breccia	Weak hematite from 42.22 - 44.5 m. Locally foliated at 45 deg. to C.A. local								
			waxy pyrite approx. 3% overall. Mottled, veined, foliated. Medium grained,								
			Dark green. Veins 45 deg. Fractures 45 deg. Fr=3/m Vns=7/m								

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample	Sample	Interval	Width	Assay / Geochem												
From	To			No.	From			To	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)								
			Moderate patchy silica Moderate pervasive chlorite Moderate pervasive k-spar Weak patchy hematite Moderate disseminated pyrite Quartz/calcite microveinlets																	
			46.6 - 46.7 m Semi massive sulfide. Pyrite veinlets approx. 1mm in foliated chloritic rock approx 30 %. Minor wispy hematite with pyrite.																	
46.7	55.95	Hornblende Feldspar Crystalline	Weakly mottled, minor quartz/calcite stockwork. Crystalline, massive. Fine-grained, dark green. Contact 45 deg. Fractures 60 deg. Fr=3/m Vns=2/m Weak patchy silica Moderate pervasive chlorite Weak pervasive carbonate Weak pervasive k-spar Moderate disseminated pyrite Moderate quartz/calcite microveinlets																	
			50.93 - 51.1 m Calcite vein. 51 - 55.95 m Local strong k-feldspar selvages up to 1 cm along 1 - 2 mm chlorite veinlets. 55.1 - 55.2 m Calcite vein.																	
55.95	88.39	Hornblende Feldspar Breccia	Strongly chloritic with intense fine quartz/calcite stockwork approx. 8 %. Local epidote rich veinlets up to 1 cm. Mottled, foliated. Medium grained, dark green. Foliation 45 deg. Fractures 45 deg. Fr=7/m Vns=10/m Weak patchy silica Moderate pervasive chlorite Moderate pervasive carbonate Moderate pervasive k-spar Moderate disseminated pyrite Intense quartz/calcite microveinlets																	
			61.5 - 67 m Minor wispy pyrite approx 7 - 8 % overall. 69.8 - 69.9 m Semi massive hematite. Hematite veinlet with minor epidote as selvage to vein, chloritic. 72 - 74 m Approx 4 - 5 % pyrite as wisps and patches. 79 - 78.15 m Calcite vein, chloritic. 81.5 - 82 m Broken core, limonitic. 82.3 - 84 m Broken core, weakly sheared, limonitic. 85 - 86 m Approx 6 % pyrite as patches and veinlets. at 87.1 m Minor fine arsenopyrite crystals and blebs.																	
88.39	106.38	Hornblende Feldspar Crystalline	Strong quartz/calcite/epidote stockwork approx. 10 %, generally as veins 1 - 2 cm thick. Crystalline, veined. Very fine grained, light gray. Veins 70 deg Fractures 60 deg. Fr=5/m Vns=15/m Moderate patchy silica Weak pervasive chlorite Weak pervasive carbonate Weak pervasive k-spar Weak disseminated pyrite Strong quartz/calcite microveinlets																	
			101.95 - 103.7 m Broken core, limonitic on fractures. 105.7 - 105.75 m Calcite vein at 45 deg. to C.A.																	
106.38	137.16	Hornblende Feldspar Breccia	Local intense k-feldspar, quartz/calcite stockwork approx. 8 %. Mottled, veined. Medium grained, dark gray. Veins 60 deg. Fractures 60 deg.																	

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample	Sample	Interval	Width	Assay / Geochem			
From	To			No.	From	To		Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
			Fr=5m Vns=10/m								
			Moderate patchy silica								
			Moderate pervasive chlorite								
			Moderate pervasive carbonate								
			Weak pervasive sericite								
			Moderate pervasive k-spar								
			Moderate disseminated pyrite								
			Quartz/calcite stockwork								
			115 - 117 m Epidote along quartz/calcite veins, pyrite approx. 3 % overall.								
			113.93 - 114.6 m Semi massive sulfide. Intense K-feldspar alteration, pyrite approx. 15 %, arsenopyrite approx. 8 % and strong chlorite.								
			At 125 m Weak sericite alteration starts and extends to bottom of hole.								
			E.O.H. 137.16 m								

TEUTON RESOURCES CORPORATION LTD.

PROPERTY: Clone Property					HOLE No.	DDH-CI-97-137						
Azimuth: 185 degrees			Dip: -65 degree	Depth:155.14 m		Date:			Logged by:ERK			
Meterage		Rock Type	Alteration, Mineralization	Sample	Sample	Interval	Assay / Geochem					
From	To	& Structure Description		No.	From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)	
1.22	17.2	Hornblende Feldspar Breccia	Local intense k-feldspar, minor quartz/calcite stockwork approx. 2 - 3 %.	61893	1.22	3	1.78					
			Stockwork, mottled, wispy. Medium grained, dark red/green. Veins 60 deg	61894	3	4.5	1.5					
			Fractures 60 deg.	61895	4.5	6	1.5					
			Frs=5/m Vns=20/m	61896	6	7.5	1.5					
			Moderate patchy silica	61897	7.5	9	1.5					
			Moderate pervasive chlorite	61898	9	10.5	1.5					
			Weak pervasive carbonate	61899	10.5	12	1.5					
			Moderate pervasive k-spar	61900	12	13	1					
			Strong stockwork hematite	61901	13	14	1					
			Quartz/calcite microveinlets	61902	14	15	1					
				61903	15	16	1					
			11.8 - 17.2 m Strong increase in hematite.	61904	16	17	1					
			15.24 - 15.9 m Strong k-feldspar/hematite/chlorite.	61905	17	18	1					
			17.2 - 28.05 m H-1 Zone. Semi massive hematite. Zone of intense chlorite,	61906	18	18.6	0.6					
			k-feldspar alteration and semi massive to massive hematite. Local narrow	61907	18.6	19.47	0.87					
			closely spaced quartz/calcite/chlorite veinlets.	61908	19.47	20	0.53					
			Veined, stockwork. Medium grained, dark red. Veins 60 deg. Fractures 60 d	61909	20	21	1					
			Frs=5/m Vns=50/m	61910	21	22	1					
			Moderate patchy silica	61911	22	23	1					
			Strong pervasive chlorite	61912	23	24	1					
			Weak pervasive carbonate	61913	24	25	1					
			Moderate patchy magnetite	61914	25	26	1					
			Moderate pervasive k-spar	61915	26	27	1					
			Intense stockwork hematite	61916	27	28	1					
			Weak disseminated pyrite	61917	28	29.5	1.5					
			Quartz/calcite microveinlets	61918	29.5	31	1.5					
				61919	31	32.5	1.5					
			18.6 - 19.47 m Semi massive hematite, minor specularite, traces visible gol	61920	32.5	34	1.5					
			Hematite approx. 40 - 50 % in intense k-feldspar alteration, weakly magnetic.	61921	34	35.5	1.5					
			19.47 - 22 m Intense dark chlorite with approx. 30 % wispy hematite.	61922	35.5	37	1.5					
			22 - 23 m Strong randomly orientated hematite stockwork.	61923	37	38.15	1.15					
			23 - 28.05 m Strong k-feldspar with approx. 20 % hematite.	61924	38.15	40	0.85					
				61925	40	41.5	1.5					
28.05	48.5	Hornblende Feldspar Breccia	Local strong k-feldspar alteration	61926	41.5	43	1.5					
			Stockwork, mottled, veined. Medium grained, dark red. Veins 45 deg.	61927	43	44.5	1.5					
			Fractures 60 deg.	61928	44.5	46	1.5					
			Frs=5/m Vns=20/m	61929	46	47.5	1.5					
			Weak patchy silica	61930	47.5	49	1.5					
			Strong pervasive chlorite	61931	49	50.5	1.5					
			Moderate pervasive carbonate	61932	50.5	52	1.5					
			Strong stockwork hematite	61933	52	53	1					
			Weak disseminated pyrite	61934	53	54	1					
			Quartz/calcite microveinlets	61935	54	55.5	1.5					
				61936	55.5	56.5	1					
			30.5 - 32.5 m Strong stockwork hematite approx. 20 %.	61937	56.5	58	1.5					
			33.22 - 43.6 m Strong epidote, both as patches and along veinlets.	61938	58	59	1					
			At 37 - 38.3 m approx. 5 % epidote	61939	59	60	1					
				61940	60	61	1					
48.5	116.55	Hornblende Feldspar Breccia	Hematite alteration consists of minor pink (hematite rich) calcite at upper	61941	61	62	1					
			contact. Strong quartz/calcite stockwork, local intense chlorite.	61942	62	63	1					
			Mottled, veined. Medium grained, dark green. Veins 45 deg. Fractures 60 d	61943	63	64	1					
			Frs=6/m Vns=10/m	61944	64	65	1					
			Moderate patchy silica	61945	65	66	1					
			Moderate pervasive chlorite	61946	66	67	1					
			Moderate pervasive carbonate	61947	67	68.5	1.5					
			Moderate pervasive k-spar	61948	68.5	70	1.5					

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample	Sample	Interval	Width	Assay / Geochem			
From	To			No.	From	To		Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
			Weak patchy pyrite	61949	70	71	1				
			Strong quartz/calcite microveinlets	61950	71	72.28	1.28				
				61951	72.28	73.5	1.22				
			55.7 - 55.75 m Pyrite vein (50 % pyrite, minor chalcopyrite)	61952	73.5	75	1.5				
			56 - 56.15 m Pyrite vein (25 % pyrite, minor chalcopyrite)	61953	75	75.92	0.92				
			60.4 - 67.5 m Intense k-feldspar, chloritic with semi massive sulfide veins.	61954	75.92	76.5	0.58				
			Local hematite rich patches.	61955	76.5	78	1.5				
			63.03 - 65 m Hornblende feldspar breccia. Stockwork, brecciated.	61956	78	79.5	1.5				
			Intense pervasive k-spar	61957	79.5	81	1.5				
			Weak stockwork hematite	61958	81	82.5	1.5				
			Moderate vein pyrite	61959	82.5	84	1.5				
			Hematite approx. 5 % in above section.	61960	84	85.5	1.5				
			64.5 - 64.25 m Minor weak magnetite.	61961	85.5	87	1.5				
			64.18 - 64.25 m Pyrite vein.	61962	87	88.5	1.5				
			66 - 67.8 m Broken core, ironitic on fractures.	61963	88.5	90	1.5				
			70.2 - 72.28 m Chlorite streaming. Black chlorite with wispy pyrite approx.	61964	90	91.5	1.5				
			8 - 10 %.	61965	91.5	93	1.5				
			75.92 - 76.4 m Hornblende feldspar breccia with intense k-feldspar alteration	61966	93	94.5	1.5				
			strong chlorite and pyrite veinlets approx. 10 % at 75.92 - 75.96 m (30 %	61967	94.5	96	1.5				
			pyrite) and 76.38 - 76.4 m (20 % pyrite).	61968	96	97.5	1.5				
			From 77 - 93.5 m Local very intense k-feldspar alteration, generally with wis	61969	97.5	99	1.5				
			black chlorite and wispy pyrite. zones of k-feldspar have pale gray mosaic	61970	99	100.5	1.5				
			texture, mottled with fragments up to 2 cm and pyrite approx. 3 - 4 %.	61971	100.5	102	1.5				
			80.5 - 80.95 m Calcite vein, strong chlorite.	61972	102	1103.5	1.5				
			At 85.95 m 1 cm calcite/pyrite veinlet	61973	103.5	105	1.5				
			95 - 99 m Strong k-feldspar as selvages up to 2 cm on each side of black	61974	105	106	1				
			chlorite veinlets from 1mm to 3 cm. Minor hematite as wisps with the K-felds	61975	106	107	1				
			alteration.	61976	107	108	1				
			107 - 108.4 m Strong intense k-feldspar alteration with pyrite veinlets up to 1	61977	108	109	1				
			cm wide at 30 deg. to C.A. Pyrite approx. 12 %.	61978	109	110	1				
			113 - 116.3 m Strong k-feldspar alteration along selvages to chlorite veinlets	61979	110	111	1				
			Alteration generally at 45 deg. to C.A. Minor wispy pyrite with the chlorite.	61980	111	112	1				
				61981	112	113	1				
116.55	117.59	Semi Massive Sulfide	S-Zone Zone of intense chlorite with massive pyrite/arsenopyrite veins up to	61982	113	114	1				
			15 cm. sulfides approx. 15 %. Veined. Medium grained, dark gray.	61983	114	115	1				
			Veins 45 deg. Fractures 35 deg.	61984	115	116	1				
			Fr=4m Vn=6/m	61985	116	116.55	0.55				
			Weak patchy silica	61986	116.55	117.59	1.34				
			Intense pervasive chlorite	61987	117.59	118	0.11				
			Moderate pervasive carbonate	61988	118	119	1				
			Intense vein pyrite	61989	119	120	1				
			Quartz/calcite microveinlets	61990	120	121	1				
				61991	121	122	1				
			116.8 - 118.83 m Arsenopyrite vein	61992	122	123	1				
			116.9 - 117.2 m Semi massive sulfide (up to 50 % pyrite/arsenopyrite, minor	61993	123	124	1				
			hematite	61994	124	125	1				
			117.48 - 117.5 m Arsenopyrite vein	61995	125	126	1				
				61996	126	127	1				
117.59	133.5	Hornblende Feldspar breccia	Very strong quartz/calcite stockwork approx. 10 %, intense chlorite, minor	61997	127	128	1				
			k-feldspar. Pyrite approx. 4 % as patches and veinlets.	61998	128	129	1				
			Mottled, veined. Medium grained, light black. Veins 60 deg. Fractures 45 d	61999	129	130	1				
			Fr=6m Vn=15/m	62000	130	131	1				
			Weak patchy silica	62001	131	132	1				
			Intense pervasive chlorite	62002	132	133	1				
			Strong pervasive carbonate	62003	133	133.5	1.5				
			Moderate pervasive k-spar	62004	133.5	134.5	1				
			Moderate disseminated pyrite	62005	134.5	135.5	1				
			Strong quartz/calcite microveinlets	62006	135.5	136.5	1				
				62007	136.5	137.33	0.83				
			126.2 - 126.4 m Semi massive sulfide. Strong chlorite with 10 % pyrite and	62008	137.33	138.27	0.84				
			approx. 2 - 3 % arsenopyrite.	62009	138.27	139	0.73				

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample	Sample	Interval	Width	Assay / Geochem			
From	To			No.	From	To		Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
			From 125.7 - 130.7 m Intense dark chlorite with wisps and occasional 1 cm patches of pyrite.	62010	139	140	1				
				62011	140	141	1				
			131.5 - 133.5 m Intense k-feldspar alteration as selvages to black chlorite and minor wispy pyrite with k-feldspar	62012	141	142	1				
				62013	142	143	1				
				62014	143	144.5	1.5				
133.5	138.27	Semi Massive Sulfide	S-Zone Intense k-feldspar alteration with massive pyrite/arsenopyrite. Vein associated with black chlorite. Minor hematite with massive sulfide section.	62015	144.5	146	1.5				
				62016	146	147.5	1.5				
				62017	147.5	149	1.5				
			133.8 - 133.7 m Pyrite vein (2 cm massive pyrite/minor arsenopyrite)	62018	149	150.5	1.5				
			133.9 - 134.05 m Semi massive sulfide, veins at 45 deg. (coarse pyrite/ arsenopyrite approx. 50 % associated with black chlorite.	62019	150.5	152	1.5				
			134.5 - 135.2 m semi massive sulfide at 45 deg to C.A. (coarse pyrite/ arsenopyrite approx. 30 % with black chlorite.	62020	152	153.5	1.5				
			137.3 - 138.25 m Semi massive sulfide (coarse pyrite/arsenopyrite/minor hematite. Sulfides approx. 30 %.	62021	153.5	155.14	1.64				
138.27	155.14	Hornblende Feldspar Breccia	Generally weak quartz/calcite stockwork. Local narrow sections of intense k-feldspar alteration. Mottled, veined. Medium grained, dark gray. Veins 60 deg. Fractures 45 deg. Frs=4/m Vns=3/m Weak patchy silica Moderate pervasive Chlorite Moderate pervasive carbonate Moderate pervasive sericite Moderate pervasive k-spar Moderate disseminated pyrite Weak quartz/calcite microveinlets.								
			143.35 - 143.4 m Calcite vein.								
			143.7 - 143.75 calcite vein.								
			From 150 - 155.14 m, Intense chlorite alteration. start of minor sericite alteration at bottom of hole.								
			From 150.5 - 155.14 m, approx. 10 % fine quartz/calcite stockwork.								
			E. O. H. 155.14 m								

TEUTON RESOURCES CORPORATION LTD.

PROPERTY: Clone Property			HOLE No.		DDH-CI-97-138								
Azimuth: 045 degrees		Dip: -45 degree		Depth: 92.86m		Date:		Logged by: ERK					
Meterage		Rock Type		Alteration, Mineralization		Sample		Interval		Assay / Geochem			
From	To	& Structure Description		No.	From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)		
		Brecciated intrusive with mosaic texture, local strong black chlorite as filling between clasts. Brecciated, foliated, Fragmental, Light gray.		62130	1.22	2	0.78	25	17	94	60		
		Foliation 45 deg. Veins 45 deg.		62131	2	3	1	210	23	94	130		
		Frs=3/m Vns=5/m		62132	3	4	1	130	17	72	110		
		Moderate patchy silica		62133	4	5	1	90	39	103	435		
		Moderate pervasive Chlorite		62134	5	6	1	140	18	79	140		
		Weak pervasive carbonate		62135	6	7	1	0.083	34	149	655		
		Moderate patchy pyrite		62136	7	8	1	0.06	208	103	2770		
		Weak quartz/calcite microveinlets		62137	8	9	1	160	30	107	305		
				62138	9	10	1	305	24	54	190		
				62139	10	11	1	20	8	5	25		
		6.1 - 9.6 m S-2a Zone. Zone of brecciation with black chlorite, minor pyrite patches and traces arsenopyrite as filling between clasts. Pyrite approx. 4 %		62140	11	12	1	0.33	81	200	425		
16	59.91	Homblende Feldspar Crystalline		62141	12	13	1	465	24	44	150		
		Intense k-feldspar alteration. Crystalline, veined. Fine grained, light gray.		62142	13	14	1	375	30	73	340		
		Veins 60 deg. Fractures 45 deg.		62143	14	15.5	1.5	5	16	53	75		
		Frs=6/m Vns=4/m		62144	15.5	17	1.5	5	12	32	40		
		Moderate patchy silica		62145	17	18.5	1.5	265	33	55	230		
		Moderate pervasive chlorite		62146	18.5	20	1.5	30	22	42	125		
		Weak pervasive carbonate		62147	20	21.5	1.5	5	15	31	30		
		Moderate pervasive k-spar		62148	21.5	23	1.5	5	19	25	50		
		Moderate disseminated pyrite		62149	23	24.5	1.5	25	15	77	30		
		Weak quartz/calcite microveinlets.		62150	24.5	25.5	1	5	13	79	35		
				62151	25.5	26.5	1	0.029	44	89	670		
				62152	26.5	27.5	1	10	13	26	90		
		25.85 - 25.97 m Mosaic textured breccia, coarse pyrite patches approx. 10 minor arsenopyrite, red limonite on fractures.		62153	27.5	29	1.5	0.048	18	44	110		
				62154	29	30.5	1.5	725	115	152	1500		
		29.8 - 29.4 m Chlorite streaming, intense black chlorite.		62155	30.5	32	1.5	0.018	21	201	90		
		46 - 46.94 m Broken core, limonitic on fractures.		62156	32	33.5	1.5	35	34	155	100		
		46.8 - 46.94 m Hematite rich calcite vein.		62157	33.5	35	1.5	40	15	101	85		
		At 47.1 m 8mm pyrite veinlet.		62158	35	36.5	1.5	5	20	88	85		
		47.25 - 47.3 m Intense k-feldspar with black chlorite at 45 to C.A.		62159	36.5	38	1.5	5	17	67	50		
		47.9 - 48.1 m Intense k-feldspar with minor black chlorite, minor hematite.		62160	38	39.5	1.5	10	18	76	60		
		49 - 49.05 m Pyrite in wispy veinlets approx. 30 %.		62161	39.5	41	1.5	15	12	165	55		
		54 - 54.35 m Calcite vein (approx. 50 % calcite veins up to 8 cm wide).		62162	41	42.5	1.5	15	18	128	10		
		56.8 - 57.1 m strong calcite stockwork approx. 50 %.		62163	42.5	44	1.5	10	20	108	35		
59.91	61.9	Sulfide - Hematite vein		62164	44	45.5	1.5	180	17	272	60		
		H-1 Zone. Zone consists of massive hematite veins, sulfide rich sections as well as intense chlorite. Veined. Medium grained, dark red.		62165	45.5	47	1.5	300	43	245	165		
		Veins 45 deg. Fractures 50 deg.		62166	47	48.5	1.5	140	58	273	105		
		Frs=7/m Vns=10/m		62167	48.5	50	1.5	45	36	105	80		
		Weak patchy silica		62168	50	51.5	1.5	15	11	69	15		
		Intense pervasive chlorite		62169	51.5	53	1.5	15	13	72	20		
		Weak pervasive carbonate		62170	53	54.5	1.5	25	19	105	130		
		Moderate pervasive k-feldspar		62171	54.5	56	1.5	15	17	19	45		
		Intense vein hematite		62172	56	57.5	1.5	10	16	16	30		
		Intense patchy pyrite		62173	57.5	59	1.5	5	21	25	45		
		Weak quartz/calcite microveinlets		62174	59	59.91	1.01	5	40	27	80		
				62175	59.91	60.87	0.96	0.37	331	2084	470		
				62176	60.87	61.9	1.03	0.245	110	27	175		
		60 - 60.35 m Massive hematite, weak magnetite.		62177	61.9	63	1.1	50	17	136	25		
		60.35 - 60.6 m Semi massive sulfide, pyrite approx. 30 %.		62178	63	64.5	1.5	85	10	65	55		
		60.6 - 60.7 m Massive hematite.		62179	64.5	65.5	1	25	19	104	65		
		60.7 - 60.87 m Semi massive sulfide, pyrite approx. 30 %.		62180	65.5	66.5	1	310	15	69	40		
		61.8 - 61.9 m Semi massive hematite.		62181	66.5	68	1.5	60	13	102	15		
61.9	64.6	Homblende Feldspar Crystalline		62182	68	69.5	1.5	35	20	40	5		
		Crystalline, veined. Fine grained, green. Veins 45 deg. Veins 60 deg.		62183	69.5	71	1.5	20	17	52	35		
		Frs=4/m Vns=4/m		62184	71	72.5	1.5	20	43	72	45		
		Weak patchy silica		62185	72	74	1.5	25	23	28	75		
		Moderate pervasive chlorite		62186	74	75	1	20	21	35	70		

TEUTON RESOURCES CORPORATION LTD.

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample	Sample	Interval	Width	Assay / Geochem			
From	To			No.	From	To		Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
			Moderate pervasive carbonate	62187	75	78.5	1.5	20	14	30	50
			Moderate pervasive k-spar	62188	76.5	77.16	0.68	15	31	56	90
			Moderate disseminated pyrite	62189	77.16	77.66	0.5	8,951	378	1180	300
			Moderate quartz/calcite microveinlets	62190	77.66	79	1.34	160	124	476	220
64.6	72.3	Hornblende Feldspar Crystalline		62191	79	80	1	160	16	127	60
			Mottled red/green, locally foliated at 45 deg. to C.A.. Local strong quartz/calc along fractures. stockwork veined, mottled, foliated. Fine grained, red/gree	62192	80	81	1	350	44	236	205
			Veins 45 deg. Fractures 60 deg.	62193	81	82	1	400	13	104	110
			Fr=4/m Vns=15/m	62194	82	83.5	1.5	300	15	87	50
			Weak patchy silica	62195	83.5	85	1.5	5	18	49	5
			Moderate pervasive chlorite	62196	85	86.5	1.5	615	64	347	20
			Moderate pervasive carbonate	62197	86.5	88	1.5	920	66	81	55
			Moderate pervasive k-spar	62198	88	89.5	1.5	10	22	17	5
			Strong stockwork hematite	62199	89.5	91	1.5	5	10	40	15
			Weak disseminated pyrite	62200	91	92.66	1.66	10	21	15	20
			Moderate quartz/calcite microveinlets								
			70.6 - 72 m Approx. 10 % blood red hematite veinlets at 40 deg to C.A.								
72.3	77.16	Hornblende Feldspar Crystalline									
			Fine 1 - 2 mm pyrite veinlets approx 2 - 3 % Crystalline, veined.								
			Fine grained, light green. Veins 45 deg. Fractures 60 deg.								
			Fr=20/m Vns=6/m								
			Weak patchy silica								
			Moderate pervasive chlorite								
			Moderate pervasive carbonate								
			Moderate pervasive k-spar								
			Weak vein hematite								
			Moderate vein pyrite								
			Moderate quartz/calcite microveinlets								
			72.3 - 74.37 m Broken core, highly broken, limonitic on fractures.								
77.16	77.56	Sulfide-Hematite vein									
			H-Zone, Zone of sulfide, massive hematite and chlorite.								
			77.16 - 77.21 m Pyrite vein, approx 20 % hematite.								
			76.21 - 76.95 m Massive hematite, strongly magnetic.								
77.56	83.4	Hornblende Feldspar Crystalline									
			Crystalline, mottled. Fine grained, light gray. Veins 45 deg. fractures 60 deg.								
			Fr=10/m vns=3/m								
			Weak patchy silica								
			Moderate pervasive chlorite								
			Moderate pervasive carbonate								
			Moderate pervasive k-spar								
			Weak patchy hematite								
			Moderate vein pyrite								
			Weak quartz/calcite microveinlets.								
			79.15 - 79.18 m Pyrite vein								
			80.7 - 80.45 m Semi massive sulfides, coarse pyrite approx 40 %, minor hematite.								
83.4	92.66	Hornblende feldspar Crystalline									
			Strong local k-feldspar to light purple color, local pyrite on fractures.								
			Stockwork, mottled, Fine grained, Red. Veins 35 deg. Fractures 60 deg.								
			Fr=10/m Vns=6/m								
			weak patchy silica								
			Moderate pervasive chlorite								
			Moderate pervasive carbonate								
			Strong pervasive k-spar								
			Strong stockwork hematite								
			Moderate disseminated pyrite								
			Moderate quartz/calcite microveinlets								

TEUTON RESOURCES CORPORATION LTD.

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample	Sample	Interval	Width	Assay / Geochem			
From	To			No.	From	To		Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
			86.7 - 86.75 m Narrow blood red hematite veinlets approx. 15 %.								
			88.09 - 88.3 m Strong k-feldspar alteration to pale green color.								
			E. O. H. 92.66 m								

TEUTON RESOURCES CORPORATION LTD.

PROPERTY: Clone Property					HOLE No.		DDH-CI-97-139						
Azimuth:		045 degrees	Dip: -65 degree		Depth:108.51 m		Date:		Logged by:ERK				
Meterage		Rock Type		Alteration, Mineralization		Sample		Sample Interval		Assay / Geochem			
From	To			& Structure Description		No.	From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
1.22	77.8	Hornblende Feldspar Crystalline		Wealdy foliated, local intense k-feldspar alteration, local brecciation and filling with black chlorite. Limonitic on fractures. Mottled, crystalline, foliated.		62201	1.22	3	1.78	25	26	105	125
				Medium grained, light grey. Fractures 45 deg. Foliation 40 deg.		62202	3	4	1	50	18	109	45
				Fr=8/m Vns=3/m		62203	4	5	1	25	18	82	40
				Moderate patchy silica		62204	5	6	1	5	19	64	55
				Moderate pervasive chlorite		62205	6	7	1	10	18	86	50
				Weak pervasive carbonate		62206	7	8	1	55	14	6	20
				Moderate pervasive k-spar		62207	8	9	1	370	16	9	105
				Moderate patchy pyrite		62208	9	10	1	10	11	3	60
				Weak quartz/calcite microveins		62209	10	11	1	5	12	3	20
				7.8 - 12 m S-Zone. Weak zone with weak mosaic texture.		62210	11	12	1	60	14	6	25
				8.1 - 8.8 m Approx. 7 % pyrite/trace arsenopyrite as coarse patches up to 5 mm.		62211	12	13	1	35	9	4	70
				17.5 - 19 m S-Zone. Mosaic textured, weak pyrite veinlets.		62212	13	14	1	100	10	3	15
				At 17.55 - 17.7 m and 18.81 - 19 m, minor arsenopyrite veinlets up to 5 mm.		62213	14	15	1	45	8	2	5
				Sulfides approx. 5 %		62214	15	16	1	490	9	6	5
				From 12 m and down hole, quartz/calcite approx. 5 % overall.		62215	16	17	1	70	14	60	40
				31.24 - 31.34 m Calcite vein.		62216	17	17.5	0.5	45	12	74	50
				31.5 - 31.55 m Calcite vein.		62217	17.5	19	1.5	960	74	102	1865
				40.4 - 41.18 Broken core, limonitic on fractures.		62218	19	20	1	240	14	109	140
				40.95 - 41.05 m Calcite vein.		62219	20	21.5	1.5	10	19	54	135
				46.38 - 46.48 m Calcite vein, 4 cm vein at 30 deg. to C.A.		62220	21.5	23	1.5	5	17	41	90
				51.5 - 52.73 m Mosaic textured with black chlorite		62221	23	24.5	1.5	410	75	63	60
				54 - 55.15 m Stringer Zone, semi massive sulfide. Arsenopyrite veinlets		62222	24.5	26	1.5	20	23	27	90
				with minor pyrite approx. 15 %. Locally mosaic textured, veinlets up to 2 cm across.		62223	26	27.5	1.5	60	21	40	135
				At 69 m, start of weak hematite alteration.		62224	27.5	29	1.5	30	15	66	145
				71 - 77 m Intense k-feldspar alteration along selvages to chlorite veinlets.		62225	29	30.5	1.5	120	32	69	750
				K-feldspar alteration zones at 40 deg. to C.A.		62226	30.5	32	1.5	75	17	39	190
				At 72 - 76 m Wispy pyrite approx. 3 % in K-feldspar zones.		62227	32	33.5	1.5	0.036	24	67	225
						62228	33.5	35	1.5	40	21	48	190
						62229	35	36.5	1.5	20	18	50	50
						62230	36.5	38	1.5	25	16	39	110
						62231	38	39.5	1.5	10	18	37	115
						62232	39.5	41	1.5	15	17	37	115
77.8	79	Hornblende Feldspar Crystalline		H-Zone. Weak zone of hematite veinlets, minor quartz/calcite/chlorite veinlet		62233	41	42.5	1.5	20	19	24	110
				Stockwork mottled, Veined. Fine grained, light red. veins 45 deg. Fracture 45 deg. Fr=6/m Vns=6/m		62234	42.5	44	1.5	5	13	41	20
				Weak patchy silica		62235	44	45.5	1.5	35	18	56	90
				Moderate pervasive chlorite		62236	45.5	47	1.5	75	18	102	55
				Moderate pervasive carbonate		62237	47	48.5	1.5	120	16	77	30
				Strong pervasive k-spar		62238	48.5	50	1.5	65	38	38	335
				Strong stockwork hematite Weak disseminated pyrite		62239	50	51	1	0.056	66	190	545
				Weak quartz/calcite microveinlets		62240	51	52	1	600	46	78	85
						62241	52	53	1	760	104	167	155
						62242	53	54	1	310	55	84	80
				78.6 - 78.9 m Hematite vein.		62243	54	55.5	1.5	0.242	1729	785	3.37
						62244	55.5	56.5	1	70	31	117	270
79	81.44	Hornblende Feldspar Crystalline		Local intense k-feldspar alteration to pink/light purple color. Approx. 2 % quartz/calcite stockwork. Mottled, stockwork. Fine grained, light red/green.		62245	56.5	58	1.5	15	14	79	80
				Fractures 45 deg. Veins 40 deg.		62246	58	59.5	1.5	45	25	151	50
				Fr=10/m Vns=6/m		62247	59.5	61	1.5	10	13	78	25
				Weak patchy silica		62248	61	62.5	1.5	25	15	77	35
				Moderate pervasive chlorite		62249	62.5	64	1.5	20	13	64	60
				Moderate pervasive carbonate		62250	64	65.5	1.5	50	19	147	45
				Moderate pervasive k-spar		62251	65.5	67	1.5	25	14	142	30
				Moderate stockwork hematite		62252	67	68.5	1.5	10	15	192	20
				Weak disseminated pyrite		62253	68.5	70	1.5	240	41	381	135
				Moderate quartz/calcite microveins		62254	70	71.5	1.5	100	62	543	665
						62255	71.5	73	1.5	455	48	485	680
						62256	73	74.5	1.5	220	32	143	600

TEUTON RESOURCES CORPORATION LTD.

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample	Sample	Interval	Width	Assay / Geochem			
From	To			No.	From	To		Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
			89.8 - 90.1 m Broken core, limonitic	62257	74.5	76	1.5	560	94	125	2250
				62258	76	77.5	1.5	5	31	40	40
91.44	95.55	Hornblende Feldspar Crystalline	Zone of weak k-feldspar alteration. Approx. 10 % blood red hematite stringer plus moderately intense chlorite. Minor coarse blebs of pyrite in hematite stringers. Mottled, stockwork. Fine grained, light red/green.	62259	77.5	78.5	1	5	145	71	110
				62260	78.5	79	1.5	555	383	63	360
				62261	79	80	1	40	213	60	240
			Veins 45 deg. Veins 20 deg.	62262	80	81	1	145	109	518	55
			Fr=10/m Vns=20/m	62263	81	82.5	1.5	30	95	141	75
			Weak patchy silica	62264	82.5	84	1.5	665	23	95	30
			Moderate pervasive chlorite	62265	84	85.5	1.5	150	9	62	15
			Moderate pervasive carbonate	62266	85.5	87	1.5	5	6	42	5
			Moderate pervasive k-spar	62267	87	88.5	1.5	5	5	12	10
			Strong vein hematite	62268	88.5	90	1.5	5	9	39	15
			Weak disseminated pyrite	62269	90	91.44	1.44	5	19	12	15
			Weak quartz/calcite microveinlets	62270	91.44	92	0.56	30	24	18	15
				62271	92	93	1	485	243	216	265
			92.15 - 92.17 m Hematite vein.	62272	93	94	1	45	169	843	135
			94.49 - 95.3 m Semi massive hematite, approx 30 % hematite.	62273	94	95	1	775	69	587	50
			95.5 - 95.55 m Hematite vein.	62274	95	96	1	0.066	37	35	70
			95.55 - 95.65 m Broken core.	62275	96	97	1	220	29	83	35
				62276	97	98.5	1.5	20	17	62	25
95.55	108.51	Hornblende Feldspar Crystalline	Local intense k-feldspar. Mottled, stockwork. Fine grained, light red/green.	62277	98.5	100	1.5	75	16	174	20
			Fractures 60 deg. Veins 45 deg.	62278	100	101.5	1.5	15	10	54	15
			Fr=15/m Vns=6/m	62279	101.5	103	1.5	5	9	91	15
			weak patchy silica	62280	103	104.5	1.5	15	11	38	15
			Moderate pervasive chlorite	62281	104.5	106	1.5	195	23	105	30
			Moderate pervasive k-spar	62282	106	107.5	1.5	355	37	16	45
			Strong stockwork hematite	62283	107.5	108.5	1	25	15	321	20
			Weak disseminated pyrite								
			Weak quartz/calcite microveinlets								
			From 95.55 m to the end of the hole, core is highly fractured and locally highly limonitic.								
			102.2 - 102.5 m Shear zone.								
			105.26 - 106.4 m Broken Core, limonitic.								
			At 108.4 m Narrow blood red hematite veinlets up to 5 mm.								
			E. O. H. 108.51 m								

TEUTON RESOURCES CORPORATION LTD.

PROPERTY: Clone Property						HOLE No.		DDH-CI-97-140					
Azimuth: 010 degrees			Dip: -45 degree		Depth: 143.13 m		Date:		Logged by: ERK				
Meterage		Rock Type	Alteration, Mineralization			Sample	Sample	Interval	Assay / Geochem				
From	To		& Structure Description			No.	From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
1.52	88.2	Andesite Lithic Tuff	Limonitic on fractures, clasts approx. 60% up to 4 cm in size. Weak quartz/calcite stockwork, foliated at 30 deg to C.A. Local pyrite rich sections, pyrite approx. 3% overall. Local very intense k-feldspar alteration.			62022	1.52	3	1.48	40	40	188	130
			Fragmental, foliated. Clasts, light gray. Veins 45 deg. Fractures 60 deg.			62023	3	4.5	1.5	35	19	55	50
			Frs=5/m Vns=3/m			62024	4.5	6	1.5	5	20	84	50
			Weak patchy silica			62025	6	7.5	1.5	90	26	81	90
			Moderate pervasive chlorite			62026	7.5	9	1.5	360	24	123	95
			Weak patchy sericite			62027	9	10	1	15	26	295	95
			Moderate pervasive k-spar			62028	10	11.5	1.5	10	22	217	90
			Moderate disseminated pyrite			62029	11.5	13	1.5	25	17	86	75
			Quartz/calcite microveinlets			62030	13	14.5	1.5	15	19	108	65
						62031	14.5	16	1.5	140	29	172	170
						62032	16	17.5	1.5	15	34	168	105
						62033	17.5	19	1.5	45	27	299	115
			9 - 9.4 m Approx. 10% pyrite as veinlets approx. 5 mm in width.			62034	19	20.5	1.5	15	28	108	40
			15.4 - 16 m Broken core, very limonitic, poor recovery.			62035	20.5	22	1.5	20	28	39	50
			16 - 20.7 m Intense k-feldspar alteration with moderately strong sericite.			62036	22	23.5	1.5	30	37	54	65
			21.1 - 21.5 m Calcite vein, approx. 30% quartz/calcite with strong chlorite.			62037	23.5	25	1.5	20	31	47	60
			From 24.3 - 46.5 m Approx. 10% quartz/calcite stockwork.			62038	25	26	1	65	24	44	40
			26 - 27.13 m Pyrite approx. 10%.			62039	26	27	1	75	29	41	35
			26.95 - 27.13 m Approx. 20% pyrite.			62040	27	28	1	310	53	48	15
			35.4 - 35.8 m Calcite vein, approx. 40% quartz/calcite/minor chlorite.			62041	28	29	1	35	24	56	15
			42.1 - 42.37 m Sulfide-hematite vein. Approx. 50% coarse cube pyrite in brownish hematite? (possibly sphalerite)			62042	29	30.5	1.5	5	25	63	5
			43 - 46 m Approx. 5% pyrite as fine veinlets approx. 1 - 2 mm.			62043	30.5	32	1.5	5	24	20	15
			45.05 - 45.52 m 50% calcite as filling in brecciated tuff.			62044	32	33.5	1.5	10	20	19	15
			49 - 52 m Strong quartz/calcite stockwork approx. 10%.			62045	33.5	35	1.5	10	23	77	10
			46.4 - 47.1 m Strongly limonitic.			62046	35	36.5	1.5	5	22	70	10
			52.1 - 55.7 m Fine wispy pyrite veinlets approx. 5 - 7%.			62047	36.5	38	1.5	10	17	1	10
			62.3 - 62.6 m Calcite vein. Calcite approx. 50% as filling in brecciated tuff.			62048	38	39.5	1.5	10	37	17	15
			64.2 - 66.5 m Approx. 3% fine pyrite veinlets and patches.			62049	39.5	41	1.5	5	13	1	5
			From 62.6 - 85.34 m Generally weak quartz/calcite stockwork.			62050	41	41.5	1.5	5	19	9	20
						62051	41.5	42.6	1.1	150	160	2494	180
						62052	42.6	44	1.4	5	14	6	10
88.2	90.9	Mudstone	Highly foliated, strong calcite stockwork, some andesite lapilli tuff beds (highly contorted). Contorted, foliated. Medium grained, dark black.			62053	44	45.42	1.42	0.03	22	73	55
			Foliation 45 deg. veins 30 deg.			62054	45.42	46.5	0.98	0.038	26	68	55
			Frs=3/m Vns=20/m			62055	46.5	47	1.5	25	38	137	40
			Weak patchy silica			62056	47	48	1	15	31	196	30
			Weak pervasive chlorite			62057	48	49	1	10	32	31	25
			Moderate pervasive carbonate			62058	49	50.5	1.5	15	28	15	10
			Weak disseminated Pyrite			62059	50.5	52	1.5	10	23	3	10
			Strong quartz/calcite microveinlets			62060	52	53	1	80	46	203	55
						62061	53	54	1	75	45	210	85
						62062	54	55	1	30	47	150	90
90.9	113.5	Andesite Lithic Tuff	Strong quartz/calcite stockwork approx. 10%. Minor ash tuff beds up to 20 cm. Foliated, bedded. Bedding 45 deg. veins 30 deg.			62063	55	56	1	80	43	221	55
			Frs=3/m Vns=10/m			62064	56	57.5	1.5	240	22	63	40
			Moderate patchy silica			62065	57.5	59	1.5	120	16	36	15
			Moderate pervasive chlorite			62066	59	60.5	1.5	45	29	89	20
			Moderate pervasive carbonate			62067	60.5	62	1.5	75	19	3	20
			Moderate pervasive k-spar			62068	62	63.5	1.5	5	17	16	20
			Moderate disseminated pyrite			62069	63.5	65	1.5	20	28	86	10
			Strong quartz/calcite microveinlets			62070	65	66.5	1.5	20	24	16	5
						62071	66.5	68	1.5	30	24	56	5
						62072	68	69.5	1.5	5	20	33	10
			90.9 - 91.4 m Strong k-feldspar with 20% calcite, pyrite approx. 7%.			62073	69.5	71	1.5	5	22	107	10
			97.6 - 98.05 m Gray calcite with light green chlorite, patches of pyrite approx. 3% (narrow breccia zone).			62074	71	72.5	1.5	10	56	211	30
						62075	72.5	74	1.5	5	16	14	10
			101.4 - 104 m Pyrite approx. 5% as coarse veinlets up to 2 cm as well as wispy stringers.			62076	74	75.5	1.5	5	14	6	5
						62077	75.5	77	1.5	5	11	80	5

TEUTON RESOURCES CORPORATION LTD.

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample No.	Sample From	Interval To	Width	Assay / Geochem				
From	To							Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)	
				62078	77	78.5	1.5	5	16	137	25	
113.5	119	Breccia Zone	Zone is light green andesitic fragments in a gray to tan calcite matrix.	62079	78.5	80	1.5	5	14	242	15	
			Fragments approx. 60 - 70 %. Later quartz/calcite veins at 80 deg. to C.A.	62080	80	81.5	1.5	5	17	402	15	
			Traces arsenopyrite, traces chalcopyrite, minor pyrite.	62081	81.5	83	1.5	5	14	161	10	
			Braciated, veined, foliated. Clasts, light green. Foliation 45 deg. Fractures 45 deg.	62082	83	84.5	1.5	10	21	127	50	
			Fr=4/m Vns=10/m	62083	84.5	86	1.5	15	19	175	45	
			Weak patchy silica	62084	86	87.5	1.5	35	22	324	60	
			Strong pervasive chlorite	62085	87.5	89	1.5	50	27	136	140	
			Strong pervasive carbonate	62086	89	90.5	1.5	65	21	113	70	
			Moderate pervasive k-feldspar	62087	90.5	92	1.5	135	30	132	70	
			Moderate disseminated pyrite	62088	92	93.5	1.5	5	14	32	10	
			Strong quartz/calcite microveinlets.	62089	93.5	95	1.5	5	18	27	15	
				62090	95	96.5	1.5	5	15	44	20	
				62091	96.5	98	1.5	80	44	46	90	
119	128.95	Andesite Lithic Tuff	Weak quartz/calcite stockwork. Clasts approx. 80 %, up to 8 cm in size.	62092	98	99.5	1.5	5	17	57	25	
			Minor mudstone beds up to 40 cm wide, at 121.85 - 122.15 and 126.8 - 127.	62093	99.5	101	1.5	5	12	122	15	
			Fragmental, foliated.	62094	101	102	1	110	51	359	70	
			Clasts, light gray. Foliation 45 deg. Fractures 45 deg.	62095	102	103	1	30	38	336	70	
			Fr=4/m Vns=2/m	62096	103	104	1	135	39	231	70	
			Weak patchy silica	62097	104	105	1	30	6	3	15	
			Moderate pervasive chlorite	62098	105	106.5	1.5	5	3	5	5	
			Moderate pervasive carbonate	62099	106.5	108	1.5	10	9	10	5	
			Weak pervasive k-spar	62100	108	109.5	1.5	5	15	27	30	
			Weak disseminated pyrite	62101	109.5	111	1.5	5	14	55	10	
			Weak quartz/calcite microveinlets	62102	111	112	1	5	10	12	10	
				62103	112	113	1	5	15	2	25	
			124.15 - 124.25 m Calcite vein.	62104	113	114	1	5	15	77	10	
				62105	114	115	1	25	17	183	20	
128.95	143.13		Mudstone	Highly contorted, sheared, graphitic with strong calcite (possibly recrystallized thin limestone beds). Bedded, contorted, foliated. Medium grained, dark black. Bedding 30 deg.	62106	115	118	1	45	18	487	25
				Weak pervasive chlorite	62107	116	117	1	85	13	701	15
				Moderate pervasive carbonate	62108	117	118	1	30	12	365	5
		Moderate disseminated pyrite		62109	118	119	1	10	15	90	10	
		Strong quartz/calcite microveinlets		62110	119	120.5	1.5	35	20	140	25	
				62111	120.5	122	1.5	80	18	286	20	
				62112	122	123.5	1.5	550	28	243	20	
				62113	123.5	125	1.5	60	17	35	15	
		136.3 - 136.8 m Andesite lithic tuff, fragmental.		62114	125	126.5	1.5	15	13	108	10	
		138.6 - 139.2 m Andesite lithic tuff, fragmental		62115	126.5	128	1.5	20	11	68	20	
				62116	128	129.5	1.5	5	13	84	20	
		E. O. H. 143.13 m		62117	129.5	131	1.5	5	17	68	50	
				62118	131	132.5	1.5	5	15	66	45	
				62119	132.5	134	1.5	5	14	77	50	
				62120	134	135.5	1.5	5	17	64	55	
				62121	135.5	137	1.5	5	14	58	30	
				62122	137	138.5	1.5	5	15	58	30	
				62123	138.5	140	1.5	5	22	202	45	
				62124	140	141.5	1.5	5	16	61	55	
				62125	141.5	143	1.5	10	14	63	40	
			62126	143	144.5	1.5	5	15	69	40		
			62127	144.5	146	1.5	5	13	60	35		
			62128	146	147.5	1.5	5	13	67	65		
			62129	147.5	148.13	0.63	15	15	80	75		

TEUTON RESOURCES CORPORATION LTD.

PROPERTY: Clone Property						HOLE No.		DDH-CI-97-141				
Azimuth: 010 degrees		Dip: -55 degree		Depth: 161.54 m		Date:		ERK				
Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample No.	Sample From	Sample To	Interval	Width	Assay / Geochem			
From	To			No.	From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)	
1.22	39.67	Andesite Lithic Tuff	Local intense k-feldspar alteration. Minor quartz/calcite stockwork, local strong chlorite. Fragmental, mottled, foliated. Clasts, light gray. Veins 45 deg. Foliation 40 deg.	62284	1.22	2	0.78					
				62285	2	3.5	1.5					
				62286	3.5	5	1.5					
				62287	5	6.5	1.5					
				62288	6.5	8	1.5					
				62289	8	9.5	1.5					
				62290	9.5	11	1.5					
				62291	11	12.5	1.5	10	18	113	35	
				62292	12.5	14	1.5	120	27	134	105	
				62293	14	15.5	1.5	10	23	81	40	
				62294	15.5	17	1.5	20	40	63	60	
				62295	17	18.5	1.5	40	29	52	40	
				62296	18.5	20	1.5	20	24	66	45	
				62297	20	21.5	1.5	5	27	63	45	
				62298	21.5	23	1.5	25	31	56	50	
				62298	23	24.5	1.5	115	38	121	70	
				62300	24.5	26	1.5	115	21	49	20	
39.67	40.6	Pyroxene Porphyry	Weak quartz/calcite, lower contact has 30 cm breccia zone with calcite cementing tuff fragments. Porphyritic, coarse grained, dark gray. Contact 30 deg. Veins 60 deg.	62301	26	27.5	1.5	20	18	25	10	
				62302	27.5	29	1.5	25	13	2	5	
				62303	29	30.5	1.5	25	13	2	10	
				62304	30.5	32	1.5	60	16	2	15	
				62305	32	33.5	1.5	5	11	2	10	
				62306	33.5	35	1.5	5	12	2	5	
				62307	35	36.5	1.5	60	20	66	5	
				62308	36.5	38	1.5	5	10	2	5	
40.6	76.2	Andesite Lithic Tuff	Angular clasts up to 10 cm approx. 40 %, weak quartz/calcite stockwork. Fragmental, mottled. Clasts, dark gray.	62309	38	38.5	1.5	5	10	1	5	
				62310	38.5	41	1.5	5	13	2	20	
				62311	41	42.5	1.5	5	18	56	10	
				62312	42.5	44	1.5	565	27	318	10	
				62313	44	45.5	1.5	5	12	3	10	
				62314	45.5	47	1.5	5	11	4	5	
				62315	47	48.5	1.5	10	11	18	10	
				62316	48.5	50	1.5	330	19	128	15	
				62317	50	51.5	1.5	5	16	51	5	
				62318	51.5	53	1.5	5	8	7	5	
				62319	53	54.5	1.5	5	8	13	5	
				62320	54.5	56	1.5	40	15	189	10	
				62321	56	57.5	1.5	5	20	47	10	
				62322	57.5	59	1.5	15	18	3	5	
				62323	59	60.5	1.5	30	17	6	5	
				62324	60.5	62	1.5	25	16	2	5	
				62325	62	63.5	1.5	10	23	17	5	
				62326	63.5	65	1.5	5	10	49	5	
				62327	65	66.5	1.5	65	27	178	15	
				62328	66.5	68	1.5	15	17	95	15	
				62329	68	69.5	1.5	5	12	48	5	
				62330	69.5	71	1.5	5	13	63	5	
				62331	71	72.5	1.5	5	17	66	20	
				62332	72.5	74	1.5	5	9	82	10	
				62333	74	75.5	1.5	5	10	75	15	
				62334	75.5	77	1.5	5	16	135	25	
				62335	77	78.5	1.5	5	23	80	35	
				62336	78.5	80	1.5	5	23	97	25	
				62337	80	81.5	1.5	5	24	110	25	
				62338	81.5	83	1.5	5	18	91	25	
				62339	83	84.5	1.5	5	17	145	10	

TEUTON RESOURCES CORPORATION LTD.

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample	Sample	Interval	Width	Assay / Geochem				
From	To			No.	From	To		Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)	
104	111.65	Mudstone/Andesite Lithic Tuff	Interbedded mudstone/tuff with beds up to 2 m. of tuff in mudstone.	62340	84.5	86	1.5	10	24	137	20	
			Bedded, foliated. Clasts/fine grained, black. Bedding 45 deg. Fractures 60 deg. Frs=5/m Vns=2/m	62341	86	87.5	1.5	5	28	92	30	
			Weak pervasive chlorite	62342	87.5	89	1.5	5	26	109	30	
			Moderate pervasive sericite	62343	89	90.5	1.5	10	21	81	25	
			Weak disseminated pyrite	62344	90.5	92	1.5	10	27	216	40	
			Weak quartz/calcite microveinlets	62345	92	93.5	1.5	15	20	90	35	
				62346	93.5	95	1.5	35	31	207	45	
				62347	95	96.5	1.5	5	17	99	25	
				62348	96.5	98	1.5	45	21	58	75	
				62349	98	99.5	1.5	70	21	106	75	
			62350	99.5	101	1.5	15	20	120	55		
111.65	137	Andesite Lithic Tuff	Strong quartz/calcite stockwork approx. 8 %, pyrite approx. 1 - 2 %. Local black chlorite patches. Mottled, fragmental. Clasts, light gray. Veins 45 deg Fractures 45 deg. Frs=8/m Vns=15/m	62351	101	102.5	1.5	15	22	70	40	
			Weak patchy silica	62352	102.5	104	1.5	60	28	80	80	
			Moderate pervasive chlorite	62353	104	105.5	1.5	90	20	47	125	
			Moderate pervasive carbonate	62354	105.5	107	1.5	90	25	106	85	
			Weak pervasive sericite	62355	107	108.5	1.5	185	37	328	140	
			Weak pervasive k-spar	62356	108.5	110	1.5	60	26	183	130	
			weak disseminated pyrite	62357	110	111.5	1.5	25	26	96	80	
			Moderate quartz/calcite microveinlets	62358	111.5	113	1.5	25	15	39	70	
				62359	113	114.5	1.5	40	11	19	20	
				62360	114.5	116	1.5	185	13	10	20	
137	161.54	Tuff	andesitic, bedded at 45 deg. to C.A., weakly pyritic. Approx. 10 % quartz/calcite stockwork, minor sections with fragments. Bedded, mottled. Medium grained, dark gray. Veins 45 deg. Fractures 45 deg. Frs=4/m Vns=5/m	62361	116	117.5	1.5	110	20	63	30	
			Weak patchy silica	62362	117.5	119	1.5	450	25	89	54	
			Moderate pervasive chlorite	62363	119	120.5	1.5	375	16	30	20	
			Moderate pervasive carbonate	62364	120.5	122	1.5	35	19	31	25	
			Weak pervasive k-spar	62365	122	123.5	1.5	20	18	18	25	
			weak disseminated pyrite	62366	123.5	125	1.5	15	36	13	45	
			Moderate quartz/calcite microveinlets	62367	125	126.5	1.5	15	32	17	40	
				62368	126.5	128	1.5	35	24	50	30	
				62369	128	129.5	1.5	10	20	5	15	
				62370	129.5	131	1.5	25	15	58	30	
			62371	131	132.5	1.5	20	16	68	15		
			62372	132.5	134	1.5	5	18	58	5		
			62373	134	135.5	1.5	5	18	49	10		
			62374	135.5	137	1.5	5	18	31	10		
			62375	137	138.5	1.5	10	17	36	10		
			62376	138.5	140	1.5	175	21	78	15		
			62377	140	141.5	1.5	0.207	18	118	10		
			62378	141.5	143	1.5	205	24	128	25		
			62379	143	144.5	1.5	65	23	52	25		
			62380	144.5	146	1.5	20	18	42	10		
			62381	146	147.5	1.5	10	18	74	10		
			62382	147.5	149	1.5	5	18	28	10		
			62383	149	150.5	1.5	5	17	48	5		
			62384	150.5	152	1.5	15	18	189	25		
			62385	152	153.5	1.5	80	20	489	45		
			62386	153.5	155	1.5	40	21	101	70		
			62387	155	156.5	1.5	40	18	49	25		
			62388	156.5	158	1.5	10	18	62	20		
			62389	158	159.5	1.5	5	12	14	5		
			62390	159.5	161.54	1.5	10	13	24	20		

TEUTON RESOURCES CORPORATION LTD.

PROPERTY: Clone Property					HOLE No. DDH-CI-97-143						
Azimuth: 160 degrees		Dip: -55 degree		Depth: 106.68 m		Date:	Logged by: ERK				
Meterage From To	Rock Type	Alteration, Mineralization & Structure Description	Sample No.	Sample Interval		Assay / Geochem					
				From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)	
0.91	33.6	Hornblende Feldspar Crystalline	Local intense k-feldspar alteration, local quartz/calcite/epidote veins	62480	0.91	3	2.09	0.072	74	62	55
			Minor local quartz/calcite/chlorite veinlets.	62481	3	4.5	1.5	85	82	72	35
			Stockwork, mottled. Fine grained, dark red. Veins 80 deg. Fractures 60 deg	62482	4.5	6	1.5	200	93	118	30
			Frs=10/m Vns=3/m	62483	6	7.5	1.5	260	224	83	50
			Moderate patchy silica	62484	7.5	9	1.5	35	62	77	60
			Moderate pervasive chlorite	62485	9	10.5	1.5	40	91	177	60
			Weak pervasive carbonate	62486	10.5	12	1.5	20	44	186	25
			Moderate pervasive k-spar	62487	12	13.5	1.5	15	21	197	15
			Strong stockwork hematite	62488	13.5	15	1.5	20	23	183	10
			Weak disseminated pyrite	62489	15	16.5	1.5	35	43	320	25
			Weak quartz/calcite microveinlets	62490	16.5	18	1.5	25	43	315	30
				62491	18	19.5	1.5	10	40	169	5
			0.91 - 6.8 m Brick red hematite in highly k-feldspar altered rocks.	62492	19.5	21	1.5	20	33	85	15
			6.8 - 7.62 m Very intense k-feldspar with approx. 10 % quartz/calcite veinlets	62493	21	22.5	1.5	30	33	365	25
			22 - 33 m Local, very intense k-feldspar, generally weak hematite stockwork	62494	22.5	24	1.5	565	35	321	40
			33 - 33.1 m Calcite vein, 40.5 pink calcite	62495	24	25.5	1.5	55	31	187	15
				62496	25.5	27	1.5	35	23	209	10
33.6	106.68	Hornblende Feldspar Crystalline	Generally weak quartz/calcite stockwork, local intense chlorite foliated at 70 deg. to the C.A. Local weak quartz/calcite/epidote veinlets.	62497	27	28.5	1.5	340	90	475	60
			Mottled, crystalline, foliated. Medium grained, green. veins 60 deg. fracture	62498	28.5	30	1.5	150	92	109	95
			60 deg.	62499	30	31.5	1.5	120	65	127	105
			Frs=6/m Vns=5/m	62500	31.5	33	1.5	50	47	143	35
			Weak patchy silica	66001	33	34.5	1.5	115	173	181	210
			Moderate pervasive chlorite	66002	34.5	36	1.5	95	169	150	210
			Weak pervasive carbonate	66003	36	37.5	1.5	0.038	46	609	120
			Moderate pervasive k-spar	66004	37.5	39	1.5	30	38	136	65
			Weak patchy hematite	66005	39	40.5	1.5	140	83	184	90
			Moderate disseminated pyrite	66006	40.5	42	1.5	20	14	110	15
			Weak quartz/calcite microveinlets	66007	42	43.5	1.5	10	9	24	15
				66008	43.5	45	1.5	5	8	6	10
				66009	45	46.5	1.5	5	10	22	20
			81.5 - 81.8 m K-feldspar alteration, black chlorite, minor hematite.	66010	46.5	48	1.5	5	11	24	15
			88.7 - 89.7 m K-feldspar alteration, black chlorite, hematite veinlets as wisps	66011	48	49.5	1.5	5	9	26	20
			89.68 - 89.7 m Hematite veinlet	66012	49.5	51	1.5	5	8	29	15
			From 91.3 - 97.51 m Local intense k-feldspar alteration.	66013	51	52.5	1.5	5	9	25	20
			98.9 - 99 m Calcite vein, 5 cm vein at 30 deg. to C.A.	66014	52.5	54	1.5	35	18	21	35
				66015	54	55.5	1.5	20	16	36	90
			E. O. H. 106.68 m	66016	55.5	57	1.5	5	13	18	85
				66017	57	58.5	1.5	85	47	42	50
				66018	58.5	60	1.5	540	57	118	65
				66019	60	61.5	1.5	15	11	59	15
				66020	61.5	63	1.5	10	12	74	25
				66021	63	64.5	1.5	10	12	78	15
				66022	64.5	66	1.5	0.051	48	99	60
				66023	66	67.5	1.5	80	15	84	15
				66024	67.5	69	1.5	150	16	146	25
				66025	69	70.5	1.5	145	11	87	35
				66026	70.5	72	1.5	45	12	69	25
				66027	72	73.5	1.5	115	12	58	25
				66028	73.5	75	1.5	5	10	35	20
				66029	75	76.5	1.5	10	11	48	25
				66030	76.5	78	1.5	5	12	22	15
				66031	78	79.5	1.5	90	52	108	55
				66032	79.5	81	1.5	10	67	102	85
				66033	81	82.5	1.5	235	145	452	180
				66034	82.5	84	1.5	35	29	104	35
				66035	84	85.5	1.5	35	61	150	65

TEUTON RESOURCES CORPORATION LTD.

PROPERTY:		Clone Property		HOLE No.	DDH-CI-97-142								
Azimuth:		160 degrees		Dip: -45 degree		Depth: 122.83 m		Date:	Logged by: ERK				
Meterage		Rock Type		Alteration, Mineralization		Sample		Interval		Assay / Geochem			
From	To			& Structure Description		No.	From	To	Width	Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
0.62	5	Hornblende Feldspar Breccia		Local 5 mm chlorite veinlets, local intense k-feldspar. Mottled, stockwork.		62391	0.62	2	1.48	75	47	174	40
				Coarse grained, red. Fractures 60 deg. Veins 80 deg.		62392	2	3.5	1.5	8.198	103	186	75
				Fr=10/m Vns=10/m		62393	3.5	5	1.5	0.058	100	65	25
				Weak patchy silica		62394	5	6	1	200	140	83	75
				Moderate pervasive chlorite		62395	8	7	1	235	177	101	55
				Weak pervasive carbonate		62396	7	8	1	575	273	121	60
				Moderate pervasive k-spar		62397	8	9	1	480	166	99	85
				Moderate stockwork hematite		62398	9	10	1	275	144	92	40
				Weak disseminated pyrite		62399	10	11	1	40	48	124	30
				Weak quartz/calcite microveinlets		62400	11	12	1	185	139	621	80
						62401	12	13	1	30	32	150	20
						62402	13	14	1	60	41	326	10
				5	23.5	Hornblende Feldspar Breccia		H-Zone. Zone of intense hematite stockwork approx. 40%. Local fine pyrite veinlets approx. less than 1%. Local intense chlorite and k-feldspar alteration to light purple color. Stockwork, mottled. Coarse grained, dark red.		62403	14	15	1
Fractures 60 deg. Veins 80 deg.		62404	15					16	1	65	118	1267	55
Fr=10/m Vns=30/m		60405	16					17	1	55	448	247	55
Weak patchy silica		60406	17					18	1	165	545	84	60
Strong pervasive chlorite		60407	18					19	1	135	546	172	266
Weak pervasive carbonate		60408	19					20	1	775	549	1238	390
Moderate pervasive k-spar		60409	20					21	1	0.093	353	574	315
Intense Stockwork hematite		60410	21					22	1	620	135	976	85
Weak vein pyrite		60411	22					23	1	135	54	695	10
Weak quartz/calcite microveinlets		60412	23					24	1	20	32	261	10
		60413	24					25	1	40	28	155	10
		60414	25					26	1	25	38	231	15
		60415	26					27.5	1.5	40	40	192	15
		60416	27.5	29	1.5	110	38	209	10				
23.5	36.1	Hornblende Feldspar Breccia		Local intense k-feldspar. Stockwork, mottled. Coarse grained, red.		60417	29	30.5	1.5	55	44	149	15
				Fractures 60 deg. Veins 45 deg.		60418	30.5	32	1.5	15	29	57	15
				Fr=6/m Vns=2/m		60419	32	33.5	1.5	35	14	31	15
				Weak patchy silica		60420	33.5	35	1.5	15	12	70	10
				Moderate pervasive chlorite		60421	35	36.5	1.5	25	14	42	10
				Weak pervasive carbonate		60422	36.5	38	1.5	10	15	9	5
				Moderate pervasive k-spar		60423	38	39.5	1.5	15	16	74	15
				Strong stockwork hematite		60424	39.5	41	1.5	165	32	87	15
				Weak disseminated pyrite		60425	41	42.5	1.5	30	26	52	60
				Weak quartz/calcite microveinlets		60426	42.5	44	1.5	15	10	27	10
						60427	44	45.5	1.5	15	11	35	10
						60428	45.5	47	1.5	10	18	8	25
						60429	47	48.5	1.5	10	9	14	25
		60430	48.5	50	1.5	5	6	13	15				
36.1	45.5	Hornblende Feldspar Breccia		Local mosaic texture, local intense chlorite. Mottled, fragmental, foliated.		60431	50	52	1.5	10	6	196	15
				Fine grained, gray. Fractures 60 deg. Foliation 30 deg.		60432	52	53.5	1.5	110	8	236	15
				Fr=6/m vns=2/m		60433	53.5	55	1.5	10	7	21	15
				Weak patchy silica		60434	55	56.5	1.5	5	6	24	10
				Moderate pervasive chlorite		60435	56.5	58	1.5	5	5	3	10
				Weak pervasive carbonate		60436	58	59.5	1.5	5	7	5	10
				Weak pervasive k-spar		60437	59.5	61	1.5	5	7	15	10
				Weak vein hematite		60438	61	62.5	1.5	10	9	29	15
				Weak disseminated pyrite		60439	62.5	64	1.5	35	8	57	100
				Weak quartz/calcite microveinlets		60440	64	65.5	1.5	10	12	13	20
						60441	65.5	67	1.5	40	9	15	15
						60442	67	68.5	1.5	20	7	54	30
						60443	68.5	70	1.5	10	6	27	65
45.5	90.2	Hornblende Feldspar Crystalline		Local 1 cm wide quartz/calcite veinlets, local narrow brecciated zones to give mosaic texture. Local very intense k-feldspar with associated black chlorite and traces hematite. Crystalline, veined, mottled. Coarse grained, light gray.		60444	70	71.5	1.5	100	7	92	45
						60445	71.5	73	1.5	85	13	302	25
						60446	73	74.5	1.5	85	11	127	35

TEUTON RESOURCES CORPORATION LTD.

Meterage		Rock Type	Alteration, Mineralization & Structure Description	Sample	Sample	Interval	Width	Assay / Geochem			
From	To			No.	From	To		Au(ppb)	Co(ppm)	Cu(ppm)	As(ppm)
			Veins 60 deg. Fractures 60 deg.	60447	74.5	76	1.5	120	7	121	45
			Frs=5/m Vns=2/m	60448	76	77.5	1.5	35	12	74	365
			Weak patchy silica	60449	77.5	79	1.5	15	8	22	275
			Moderate pervasive chlorite	60450	79	80.5	1.5	350	6	87	125
			Weak pervasive carbonate	60451	80.5	82	1.5	75	8	207	90
			Moderate pervasive k-spar	60452	82	83	1.5	35	13	79	50
			Weak disseminated pyrite	60453	83	85	1.5	20	10	73	45
			Weak quartz/calcite	60454	85	86.5	1.5	65	15	129	60
				60455	86.5	87.5	1.5	60	10	158	30
			52 - 52.1 m Calcite vein	60456	87.5	88.5	1.5	50	20	19	80
			63.3 - 63.7 m Very intense k-feldspar alteration	60457	88.5	89.5	1	105	29	39	160
			From 70 - 93.9 m Intense k-feldspar alteration	60458	89.5	91	1.5	410	44	57	90
			87.9 - 88 Semi massive sulfide, coarse pyrite vein up to 30 %, in vein up to 2 cm wide.	60459	91	92.5	1.5	80	29	6	35
				60460	92.5	93.9	1.4	330	51	136	65
			88.1 - 88.2 m Semi massive sulfide, approx. 20 % pyrite as coarse blebs and veining to 2 cm.	60461	93.9	95.3	1.4	0.17	400	101	450
				60462	95.3	97	1.7	0.031	108	34	140
			89.42 - 89.5 m Pyrite vein.	60463	97	98.5	1.5	35	13	196	10
			88.72 - 88.82 m Calcite vein (pink)	60464	98.5	100	1.5	30	31	8	40
				60465	100	101.5	1.5	10	6	20	5
90.2	122.83	hornblende Feldspar Crystalline	Local intense k-feldspar alteration, minor narrow blood red hematite veinlets	60466	101.5	103	1.5	25	13	241	10
			Stockwork, mottled, brecciated. Fine grained, red. Fractures 30 deg. Veins deg.	60467	103	104.5	1.5	20	20	359	20
				60468	104.5	106	1.5	10	17	17	15
			Frs=4/m Vns=10/m	60469	106	107.5	1.5	245	48	100	50
			Moderate patchy silica	60470	107.5	109	1.5	15	12	20	10
			Moderate pervasive chlorite	60471	109	110.5	1.5	70	33	76	40
			Moderate pervasive chlorite	60472	110.5	112	1.5	30	22	122	45
			Weak pervasive carbonate	60473	112	113	1.5	0.047	28	374	20
			weak patchy magnetite	60474	113	114.5	1.5	0.078	41	777	70
			Moderate pervasive k-spar	60475	114.5	116	1.5	35	13	103	30
			Moderate stockwork hematite	60476	118	118.5	1.5	25	12	63	25
			Weak disseminated pyrite	60477	118.5	119	1.5	5	13	43	20
			Moderate quartz/calcite microveinlets	60478	119	120.5	1.5	10	10	61	25
				60479	120.5	122.83	2.33	5	14	75	15
			93.9 - 93.95 m 2 cm hematite vein at 45 deg to C.A.								
			94.6 - 95.3 m Semi massive hematite. Magnetic with minor coarse pyrite, hematite approx 60 %								
			95.3 m Very intense k-feldspar, brecciated with mosaic texture and strong chlorite between clasts. Minor 1 cm blebs of coarse pyrite.								
			99.1 - 99.12 m Hematite vein								
			104.9 - 110.5 m Hematite stockwork approx. 15 % with local magnetism.								
			Highly k-feldspar altered, appearance of breccia.								
			122.78 - 114.61 m Pyrite veinlets and patches approx. 7 %								
			114.61 - 115 m Narrow quartz/calcite/chlorite veinlets.								
			118 - 119 m Strong K-feldspar alteration.								
			119.97 - 120.06 m Calcite vein.								
			E. O. H. 122.83 m								

APPENDIX III

IP Report

GEOPHYSICAL REPORT

INDUCED POLARIZATION AND
MAGNETOMETER SURVEYS

MAIN AND C-1 GRIDS, CLONE PROJECT
STEWART AREA, BRITISH COLUMBIA

on behalf of

TEUTON RESOURCES CORP.
509 - 675 West Hastings Street
Vancouver, B.C. V6B 1N2

Field work completed:
August 14 to September 1, 1997

by

Jim Hawkins, Geophysicist
SCOTT GEOPHYSICS LTD.
4013 West 14th Ave.
Vancouver, B.C. V6R 2X3

September 8, 1997

TABLE OF CONTENTS

	page
1. Introduction	1
2. Personnel	1
3. Instrumentation and Procedures	1
4. Discussion of Results	2
4.a Main Grid	3
4.b C-1 Grid	4
5. Recommendations	5

Appendix

Statement of Qualifications rear of report

Accompanying Maps (1:2500 scale)
(vellum originals, two blackline copies of each)

Chargeability/Resistivity pseudosections (with Anomaly Bars): map roll

Main Grid - Lines 2300N to 2500N

Main Grid - Lines 2550N to 2750N

Main Grid - Lines 2800N to 3000N

Camp Grid - Lines 2000N to 2100N

C-1 Grid - Lines 550E to 1050E

C-1 Grid - Lines 1300E to 1550E

Chargeability Contour Plan Maps; n=1 Separation: map roll

Main Grid

C-1 Grid

Resistivity Contour Plan Maps; n=1 Separation: map roll

Main Grid

C-1 Grid

Total Field Magnetometer Contour Plan Map;	map roll
C-1 Grid	
Total Field Magnetometer Posted Values;	map roll
C-1 Grid	
Geophysical Interpretation Maps;	map roll
Main Grid - H Zones	
Main Grid - S Zones	
C-1 Grid - H Zones	
C-1 Grid - S Zones	

Additional materials - one copy only

One floppy disk with all survey data	envelope
--------------------------------------	----------

1. INTRODUCTION

Induced Polarization/Resistivity surveys were performed on two grids, Main and C-1, on the Clone Project, near Stewart, B.C. by Scott Geophysics Ltd. on behalf of Teuton Resources Corp. Three short lines were also surveyed on what has been designated the "Camp" grid. A Total Field Magnetometer survey was performed on the same lines as the IP on the C-1 grid. The field work was done within the period August 14 to September 1, 1997.

This report describes the instrumentation and procedures, and discusses the results of the survey.

2. PERSONNEL

Jim Hawkins, Geophysicist, was the party chief on the survey on behalf of Scott Geophysics Ltd. The Senior Geophysical Technician on the survey was Gord Stewart of Scott Geophysics. Ed Kruchkowski, Geologist was the on site representative on behalf of Teuton Resources Corp.

3. INSTRUMENTATION AND PROCEDURES

A Scintrex IPR-12 time domain, microprocessor based receiver, and a Scintrex TSQ3 3 kW transmitter were used for the induced polarization survey. In areas of very poor current electrode contact, but high resistivities (such as most of the C-1 Grid), a Hunttec LOPO transmitter was used, as it can safely transmit very low currents.

The pole-dipole electrode array was used on the Induced Polarization survey, with readings taken at an "a" spacing of 25 meters, and at "n" separations of 1 to 5. A total of 7.175 kilometers were surveyed on the Main Grid, 6.575 kilometers on the C-1 Grid, and 0.450 kilometers on the Camp Grid, for a total of 14.200 kilometers. The gap in coverage between L1050E and L1300E on the C-1 Grid was due to cliffs.

Readings were taken using a 2 second alternating square wave. The chargeability for the Mx slice (690 to 1050 milliseconds after shutoff; midpoint at 870 milliseconds) is the value that has been plotted on the accompanying plans and pseudosections.

Total Field magnetometer readings were taken every 12.5 meters on the same lines as the IP survey on the C-1 Grid only, and were corrected for diurnal drift with a base magnetometer. One IP line (L1050E) was not surveyed due to equipment malfunction. A total of 5.925 kilometers were surveyed with the Scintrex IGS units.

The survey data was processed, archived, and plotted using a Toshiba T3200SX microcomputer running proprietary software.




4. DISCUSSION OF RESULTS

Gold bearing targets in the Clone Project fall in to two main types; the hematite bearing and the sulphide bearing zones, known as the H Zones and the S Zones. The H Zone mineralization is typically made up of iron oxides, gold, minor copper and iron sulphides, and is very calcareous, with local silicification. The geophysical model target will therefore be a low chargeability/high resistivity IP anomaly indicating the lack of sulphide mineralization and higher silica content, with a coincident magnetic anomaly from the iron oxides such as magnetite and hematite. These zones can be greater than ten metres wide, with a strike length of 500 metres. Several of these types of anomalies have been identified from the geophysical surveys.

S Zone mineralization is typically semi-massive to massive pyrite, arsenopyrite, gold, and minor calcopyrite, and are lenticular in shape. The geophysical model target will therefore be a high chargeability/low resistivity IP anomaly indicating massive sulphide mineralization. Zones of massive veins up to five metres thick, with a strike length of 150 metres have been found. Several anomalies of this type have been identified from the Induced Polarization survey.

Chargeability/resistivity pseudosections are presented, with anomaly bars above areas of high chargeability or low resistivity, as one would expect in areas of sulphide mineralization. In addition, Geophysical Interpretation maps for the Main Grid and C-1 Grid correlate the IP anomalies with any magnetic trends.

The anomaly bars indicate areas of strong, moderate, and weak chargeability highs or resistivity lows as follows:

	strong
	moderate
	weak

All anomalies, unless otherwise indicated, were detected by all "n" separations (n = 1 to 5). An "n=3" over the anomaly bar, for instance, indicates an anomaly that only shows from n = 3 to 5. Chargeability and Resistivity Contour Plan maps at the n=1 separation were chosen due to the lack of overburden. Gaps in the survey data usually represent ice covered areas that prevent electrode contact.

4.a MAIN GRID

The numbers of the anomalous zones described in this section are from the Geophysical Interpretation Maps accompanying this report. The stacked Chargeability/Resistivity pseudosections should also be referred to for this section.

Seven areas of potential H Zone mineralization were detected from the IP survey, all trending northwest-southeast. Zone 1 stretches from L2750N / 2050E to L3000N / 1950E, and is characterized by a near surface (n=1) very low chargeability, moderately high resistivity anomaly. A Teuton Resources 1996 magnetic survey shows a coincident magnetic high on the north end of this zone. Beneath this zone of potential hematite mineralization, however, is an area (n=3 to 5) of high chargeability and low resistivity representing potential sulphide mineralization; an S Zone underlying an H Zone. Zone 2 is a moderate chargeability, moderate resistivity, n=1 to 2 anomaly that extends from L2650N / 1975E to L2750N / 1925E. Zone 3 is a broader (50 to 75 meters wide) anomaly with low chargeability and moderate resistivity with good depth extent (n=1 to 5), extending from L2650N / 1850E to L2800N / 1775E, where it becomes less distinct. Zone 4 stretches from L2750N / 1700E to L2850N / 1675E, and may extend further off-grid to the northwest. It is characterized by a low chargeability, moderate resistivity anomaly of moderate depth extent (n=1 to 2).

Zone 5, although on strike with Zone 3, is similar in character to Zone 2, and may represent a fault displaced extension. The zone is found from L2400N / 1950E to L2600N / 1900E, broadening to the north. Zone 6 is a shallow (n=1), low chargeability, high resistivity area on L2600N at 1725E, but does not appear to extend to adjacent lines. Zone 7, covering the southwest corner of the grid, is an area of low chargeability and high resistivity, but may represent a rock type change as opposed to a discrete anomalous zone. The area is shallow in the north (n=1 to 2), deepening to n=1 to 5 in the south.

Six zones of potential S Zone mineralization were identified on the Main Grid. Zone 1 in the northeast is more an area very high chargeability and very low resistivity than a discrete anomaly, and may represent an area of graphitic rock type. Zone 2 is a broad zone, up to 150 meters wide, of high chargeabilities and low resistivities, with good depth extent (n=1 to 5), that stretches from approximately L2700N / 2050E to L3000N / 1900E, and may extend further off-grid to both the northwest and southeast. This zone is overlain in part on the north end by the potentially hematitic Zone 1, discussed previously. Zone 3 is a shallow n=1 area on L2800N, between 1725E and 1750E of high chargeability and low resistivity.

The narrow, well defined Zone 4 anomaly of moderate to high chargeabilities and low resistivities may, in fact, be a continuation of the broader Zone 6 anomaly; the combined zones running from L2500N / 1725E to L2800N / 1600E. These zones may also continue off-grid to the northwest and to the southeast, in to an area of snow cover. Most of these zones have good depth extent of n=1 to 5. Zone 5 extends from approximately L2400N / 1850E to L2600N / 1825E and is characterized by moderate charabilities and low resistivities, and good depth extent (n=1 to 5).

Three very short lines (L2000N, L2050N, and L2100N) were surveyed between the ice flows, and the results have been presented as stacked pseudosections referred to as the "Camp" Grid. Although some high chargeabilities were recorded, the lines were too short for a meaningful interpretation to be performed.

4.b C-1 GRID

The Induced Polarization survey on the C-1 Grid produced far fewer and less distinct anomalies than that on the Main Grid. Two zones of possible hematitic mineralization were identified extending from L1050E / 2800N to L850E / 2800N (Zone 1), and from L1050E / 2675N to L850E / 2600N (Zone 2). In both cases the high resistivity anomalies are better defined than the chargeability anomalies. There is no apparent coincident magnetic anomaly.

Possible sulphide mineralization was identified in three zones. Zone 1, extending from L1550E / 2600N to L1500E / 2625N, has moderate chargeabilities and resistivities from n=1 to 5. Zone 2 is characterized by moderate chargeability and resistivity anomalies and runs from L1050E / 2300N to L850E / 2375N. The zone is deeper on the ends (n=3 to 5) and shallower in the middle (n=1 to 3). Zone 3 is the most distinct anomaly, with high chargeabilities and moderate resistivities, extending through to n=1, and stretching from L950E / 2225N to L850E / 2225N.

One further anomaly that has not been given a identifying number is located at L750E / 2725N, and may have a poorly defined extension to the east and west. This anomaly is characterized by a higher than background chargeability and a high resistivity. This anomaly could be due to sulphide mineralization, with silicification to explain the high resistivity values.

Further more subtle interpretation may be possible of the C-1 Grid geophysical surveys with the help of detailed geological and/or geochemical information.


5. RECOMMENDATIONS

Several anomalous zones fitting the geophysical models merit further investigation, and, with supporting geological and geochemical data, can be considered prime drill targets.

On the Main Grid, the H Zone 1 with the underlying S Zone 2 should be followed up, as well as the broad H Zone 3 and 5. The large areas in the northeast (S type) and southwest (H type) should be investigated, more for the possibility of eliminating the areas.

The results from the C-1 Grid are less distinct, and further geological and/or geochemical information would be essential before a possible reinterpretation of the geophysical results.

All these targets are, of course, based on the geophysical results alone, and should be confirmed or modified with additional geological and geochemical information.



Statement of Qualifications

for


Jim Hawkins, Geophysicist


of

762 Dehart Road
Kelowna, B.C. V1W 4P8

I, Jim Hawkins, hereby certify the following statements regarding my qualifications, and my involvement in the program of work described in this report.

1. The work was performed by individuals sufficiently trained and qualified for its performance.
2. I have no material interest in the property under consideration in this report, nor in the company on whose behalf the work was performed.
3. I graduated from the University of Western Ontario with a Bachelor of Science degree (Geophysics) in 1977.
4. I am a member of the Association of Professional Engineers, Geologists, and Geophysicists of Alberta (P. Geoph.).
5. I have been practicing my profession continuously as a Geophysicist since 1977.






SURVEY SPECIFICATIONS

array	pole dipole
a spacing	25 meters
n separation	1
current electrode south of potentials	
receiver	Scintrex IPR12
transmitter	Huntec LOP0
pulse time	2 seconds
Mx receive window	690-1050 msec
mid point	870 msec
contour interval	2.5 msec

GEOLOGICAL SURVEY BRANCH
ASSESSMENT REPORT

25,335

PART 2 OF 2



TEUTON RESOURCES CORP.

C-1 GRID, CLONE PROJECT
STEWART AREA, B.C.
CHARGEABILITY CONTOUR
PLAN MAP
n=1 separation

DRAWN BY: jph DATE: August/97
SCOTT GEOPHYSICS LTD.

1500E

1750E

2000E


2250E

IP SURVEY SPECIFICATIONS

receiver	Scintrex IPR12
transmitter	Scintrex TSQ3
array	pole dipole
array spacing	25 meters
array separations	1 to 5
pulse time	2 seconds
Max receive window	690-1050 msec
mid point	870 msec

3000N


3000N



potential S Zone
mineralization


2750N

2750N



2500N

2500N



2250N

2250N

1500E

1750E

2000E


2250E

GEOLOGICAL SURVEY BRANCH

SCIENTIFIC SERVICES DIVISION

25335

PART 2 OF 2



TEUTON RESOURCES CORP

MAIN GRID, CLONE PROJECT

STEWART AREA, B.C.

GEOPHYSICAL
INTERPRETATION MAP
POTENTIAL S ZONES

DRAWN BY: jph

DATE: August/97

SCOTT GEOPHYSICS LTD.

1500E

1750E

2000E

2250E

IP SURVEY SPECIFICATIONS

receiver Scintrex IPR12
transmitter Scintrex TSQ3
array pole dipole
a spacing 25 meters
n separations 1 to 5
pulse time 2 seconds
Mx receive window 690-1050 msec
mid point 870 msec

Scintrex IPR12
Scintrex TSQ3
pole dipole
25 meters
1 to 5
2 seconds
690-1050 msec
870 msec

3000N

3000N

2750N

2750N

2500N

2500N

2250N

2250E

+

+

L 3000N

+

+

+

+

+

+

+

+

+

+

+

+

+

L 2950N

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

L 2900N

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

L 2850N

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

L 2800N

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

L 2750N

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

L 2700N

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

L 2650N

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

L 2600N

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

L 2550N

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

L 2500N

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

L 2450N

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

L 2400N

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

L 2350N

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

+

L 2300N

+

+

+

+

+

+

+

+


+

+


+

SURVEY SPECIFICATIONS

array	pole dipole
a spacing	25 meters
n separation	1
current electrode south of potentials	
receiver	Scintrex IPR12
transmitter	Huntac LOPO
pulse time	2 seconds
Mx receive window	690-1050 msec
mid point	870 msec
contour interval	1, 1.5, 2, 3, 5, 7.5 ohm-m per decade



3000N
2750N
2500N
2250N
2000N



PART 2 OF 2



GEOLOGICAL SURVEY BRANCH
ASSESSMENT REPORT

25,335

TEUTON RESOURCES CORP.

C-1 GRID, CLONE PROJECT


STEWART AREA, B.C.
RESISTIVITY CONTOUR
PLAN MAP

n=1 separation

DRAWN BY: jph DATE: August/97
SCOTT GEOPHYSICS LTD.

500E	750E	1000E	1250E	1500E
+57558	+57200	+57208	+57193	
+56250	+56637	+57018	+56963	
+56891	+57720	+57062	+57022	
+56979	+56449	+56367	+57061	
+57004	+56522	+57470	+57846	
+56884	+57518	+56839	+57962	
+56873	+57276	+57140	+57451	
+56874	+57339	+57087	+56873	
+57043	+57891	+57223	+57104	
+57104	+57392	+57086	+57020	
+57040	+57293	+56834	+57241	
+57250	+57440	+57917	+57024	
+57688	+57784	+57702	+57088	
+57711	+57383	+57296	+57066	
+57711	+57982	+57073	+56840	
+57791	+57730	+57214	+57366	
+57941	+57042	+57204	+57711	
+57492	+56913	+56745	+56834	
+57394	+57555	+56412	+57011	
+57285	+56804	+56647	+57721	
+57227	+56814	+56953	+57838	
+57212	+56324	+56327	+57463	
+57288	+57022	+56927	+57320	
+57082	+57611	+57082	+57583	
+57088	+57491	+56055	+57254	
+57259	+56716	+57483	+57127	
+57272	+57250	+57335	+56813	
+57185	+56850	+57503	+57547	
+57188	+56503	+57785	+57378	
+57313	+57328	+57781	+57467	
+57694	+57483	+57534	+57081	
+57352	+57728	+57017	+56548	
+57438	+57261	+56682	+57109	
+56885	+57058	+56477	+56889	
+56339	+57436	+57020	+57047	
+56104	+57325	+56679	+57154	
+56531	+56920	+56688	+57388	
+57400	+57597	+57320	+57462	
+57598	+56808	+57012	+57718	
+56707	+56646	+56614	+56980	
+56388	+56769	+56839	+56467	
+56879	+57212	+56915	+57020	
+56773	+56892	+57045	+57563	
+56688	+57188	+56768	+57251	
+57165	+56893	+56850	+57394	
+57477	+56213	+57522	+57062	
+57585	+56870	+57589	+56845	
+56984	+56864	+57314	+56930	
+56753	+56373	+56846	+57857	
+57574	+56924	+56425	+56238	
+56343	+56389	+56380	+56445	
+56818	+57080	+57264	+57093	
+57792	+57243	+57421	+57158	
+56981	+57267	+57422	+57062	
+57788	+56878	+57387	+56320	
+57270	+57298	+57131	+57465	
+56694	+57853	+56843	+56848	
	+57408	+56348	+57347	
	+57584	+56534	+56600	
	+56073	+57189	+56894	
	+57117	+57669	+56578	
	+57967	+57174	+56621	
	+57732	+57107	+56872	
	+56341	+56442	+56739	
	+57378	+56271	+56905	
	+57871	+56445	+56521	
	+56752	+56315	+56923	
	+56537	+56649	+56908	
	+57524	+56848	+56508	


SURVEY SPECIFICATIONS
 survey magnetometer Scintrex MP4
 base magnetometer Scintrex ICS
 type proton
 posted value total field
 units gammas (nT)



GEOPHYSICAL SURVEY BRANCH
 ASSESSMENT REPORT
25,335

TEUTON RESOURCES CORP.
 C-1 GRID, CLONE PROJECT
 STEWART AREA, B.C.
 TOTAL FIELD MAGNETOMETER
 POSTED VALUES

DRAWN BY: jph DATE: August/97
 SCOTT GEOPHYSICS LTD.




IP SURVEY SPECIFICATIONS

receiver	Scintrex IPR12
transmitter	Huntec LOPO
array	pole dipole
spacing	25 meters
separations	1 to 5
pulse time	2 seconds
Mx receive window	690-1050 msec
mid point	870 msec


MAG SURVEY SPECIFICATIONS

survey magnetometer	Scintrex MP4
base magnetometer	Scintrex IGS
type	proton
stn spacing	12.5 meters

 potential S Zone mineralization

GEOLOGICAL SURVEY OF CANADA


25,335



TEUTON RESOURCES CORP.

C1 GRID, CLONE PROJECT
STEWART AREA, B.C.
GEOPHYSICAL
INTERPRETATION MAP
POTENTIAL S ZONES

DRAWN BY: jph DATE: August/97
SCOTT GEOPHYSICS LTD.




IP SURVEY SPECIFICATIONS

receiver	Scintrex IPR12
transmitter	Huntec LOPO
array	pole dipole
array spacing	25 meters
array separations	1 to 5
pulse time	2 seconds
Mx receive window	690-1050 msec
mid point	870 msec

MAG SURVEY SPECIFICATIONS


survey magnetometer	Scintrex MP4
base magnetometer	Scintrex ICS
type	proton
stn spacing	12.5 meters

 potential H Zone mineralization

M magnetic high

TEUTON RESOURCES CORP.

25,335



PART 2 OF 2

0 50 100 150 200
M E T E R S

TEUTON RESOURCES CORP.

C1 GRID, CLONE PROJECT

STEWART AREA, B.C.

GEOPHYSICAL INTERPRETATION MAP

POTENTIAL H ZONES

DRAWN BY: jph DATE: August/97

SCOTT GEOPHYSICS LTD.

1500E

1750E

2000E

2250E


SURVEY SPECIFICATIONS

array	pole dipole
a spacing	25 meters
n separation	1

current electrode east of potentials

receiver	Scintrex IPR12
transmitter	Scintrex TSQ3
pulse time	2 seconds
Mx receive window	690-1050 msec
mid point	870 msec

contour interval	1, 1.5, 2, 3, 5, 7.5
	ohm-m per decade



GEOLOGICAL SURVEY BRANCH
ASSESSMENT REPORT

25,335



PART 2 OF 2

0 50 100 150 200
M E T E R S

TEUTON RESOURCES CORP

MAIN GRID, CLONE PROJECT

STEWART AREA, B.C.
RESISTIVITY CONTOUR
PLAN MAP

n=1 separation

DRAWN BY: jph

DATE: August/97

SCOTT GEOPHYSICS LTD.

SURVEY SPECIFICATIONS


array	pole dipole
a spacing	25 meters
n separation	1
current electrode east of potentials	
receiver	Scintrex IPR12
transmitter	Scintrex TS03
pulse time	2 seconds
Mx receive window	690-1050 msecs
mid point	870 msecs
contour interval	2.5 msec

GEOLOGICAL SURVEY BRANCH
ASSESSMENT REPORT

25,335




PART 2 of 2









TEUTON RESOURCES CORP.

MAIN GRID, CLONE PROJECT
STEWART AREA, B.C.
CHARGEABILITY CONTOUR
PLAN MAP
n=1 separation

DRAWN BY: jph DATE: August/97
SCOTT GEOPHYSICS LTD.






GEOLOGICAL SURVEY BRANCH
 ASSESSMENT REPORT
 25,335

TEUTON RESOURCES CORP.
 C-1 GRID, CLONE PROPERTY
 STEWART AREA, B.C.
 CHARGEABILITY/RESISTIVITY
 PSEUDOSECTIONS
 L550E-L1050E
 DRAWN BY: jph DATE: August/97
 SCOTT GEOPHYSICS LTD.

TEUTON RESOURCES CORP.


C-1 GRID, CLONE PROJECT, STEWART AREA, B.C.
 LINE: 1300E
 INDUCED POLARIZATION SURVEY (Pole-Dipole Array)
 SCINTREX IPR-12
 SCOTT GEOPHYSICS LTD.
 August/97
 Pulse Rate: 2 sec
 Current electrode is south of receiving electrodes (heading north)
 Mx Chargeability, 690-1050 msec after shutoff



TEUTON RESOURCES CORP.
 C-1 GRID, CLONE PROPERTY
 STEWART AREA, B.C.
 CHARGEABILITY/RESISTIVITY
 PSEUDOSECTIONS
 L1300E-L1550E
 DRAWN BY: jph
 DATE: August/97
 SCOTT GEOPHYSICS LTD.

TEUTON RESOURCES CORP.


C-1 GRID, CLONE PROJECT, STEWART AREA, B.C.
 LINE: 1400E
 INDUCED POLARIZATION SURVEY (Pole-Dipole Array)
 SCINTREX IPR-12
 SCOTT GEOPHYSICS LTD.
 August/97
 Pulse Rate: 2 sec
 Current electrode is south of receiving electrodes (heading north)
 Mx Chargeability, 690-1050 msec after shutoff



25,335
 PART 2 OF 2


TEUTON RESOURCES CORP.






C-1 GRID, CLONE PROJECT, STEWART AREA, B.C.
 LINE: 1500E
 INDUCED POLARIZATION SURVEY (Pole-Dipole Array)
 SCINTREX IPR-12
 SCOTT GEOPHYSICS LTD.
 August/97
 Pulse Rate: 2 sec
 Current electrode is south of receiving electrodes (heading north)
 Mx Chargeability, 690-1050 msec after shutoff



TEUTON RESOURCES CORP.

C-1 GRID, CLONE PROJECT, STEWART AREA, B.C.
 LINE: 1550E
 INDUCED POLARIZATION SURVEY (Pole-Dipole Array)
 SCINTREX IPR-12
 SCOTT GEOPHYSICS LTD.
 August/97
 Pulse Rate: 2 sec
 Current electrode is south of receiving electrodes (heading north)
 Mx Chargeability, 690-1050 msec after shutoff





PART 2 OF 2

25,335

TEUTON RESOURCES CORP.
 MAIN GRID, CLONE PROPERTY
 STEWART AREA, B.C.
 CHARGEABILITY/RESISTIVITY
 PSEUDOSECTIONS
 L2550N-L2750N

DRAWN BY: jph DATE: August/97
 SCOTT GEOPHYSICS LTD.

TEUTON RESOURCES CORP.

MAIN GRID, CLONE PROPERTY

STEWART AREA, B.C.

CHARGEABILITY/RESISTIVITY

PSEUDOSECTIONS

L2800N-L3000N

DRAWN BY: jph

DATE: August/97

SCOTT GEOPHYSICS LTD.

TEUTON SURVEY BRANCH

PART 2 OF 2

25335


TEUTON RESOURCES CORP.

MAIN GRID, CLONE PROJECT, STEWART AREA, B.C.

LINE: 3000N

INDUCED POLARIZATION SURVEY (Pole-Dipole Array)
Scintrex IPR-12
SCOTT GEOPHYSICS LTD.
August/97

Current electrode is east of receiving electrodes (heading west)
Mx Chargeability, 690-1050 msec after shutoff



LINE: 3000N


TEUTON RESOURCES CORP.

MAIN GRID, CLONE PROJECT, STEWART AREA, B.C.

LINE: 2950N

INDUCED POLARIZATION SURVEY (Pole-Dipole Array)
Scintrex IPR-12
SCOTT GEOPHYSICS LTD.
August/97

Current electrode is east of receiving electrodes (heading west)
Mx Chargeability, 690-1050 msec after shutoff



LINE: 2950N


TEUTON RESOURCES CORP.

MAIN GRID, CLONE PROJECT, STEWART AREA, B.C.

LINE: 2900N

INDUCED POLARIZATION SURVEY (Pole-Dipole Array)
Scintrex IPR-12
SCOTT GEOPHYSICS LTD.
August/97

Current electrode is east of receiving electrodes (heading west)
Mx Chargeability, 690-1050 msec after shutoff



LINE: 2900N


TEUTON RESOURCES CORP.

MAIN GRID, CLONE PROJECT, STEWART AREA, B.C.

LINE: 2850N

INDUCED POLARIZATION SURVEY (Pole-Dipole Array)
Scintrex IPR-12
SCOTT GEOPHYSICS LTD.
August/97

Current electrode is east of receiving electrodes (heading west)
Mx Chargeability, 690-1050 msec after shutoff



LINE: 2850N


TEUTON RESOURCES CORP.

MAIN GRID, CLONE PROJECT, STEWART AREA, B.C.

LINE: 2800N


INDUCED POLARIZATION SURVEY (Pole-Dipole Array)
Scintrex IPR-12
SCOTT GEOPHYSICS LTD.
August/97

Current electrode is east of receiving electrodes (heading west)
Mx Chargeability, 690-1050 msec after shutoff




LINE: 2800N

TEUTON RESOURCES CORP.
 MAIN GRID, CLONE PROJECT, STEWART AREA, B.C.
 LINE: 2100N
 INDUCED POLARIZATION SURVEY (Pole-Dipole Array)
 SCOTT GEOPHYSICS LTD.
 Scintrex IPR-12
 Pulse Rate: 2 sec
 August/97
 Current electrode is west of receiving electrodes (heading east)
 Mx Chargeability, 690-1050 msec after shutoff




LINE: 2100N

TEUTON RESOURCES CORP.
 MAIN GRID, CLONE PROJECT, STEWART AREA, B.C.
 LINE: 2050N
 INDUCED POLARIZATION SURVEY (Pole-Dipole Array)
 SCOTT GEOPHYSICS LTD.
 Scintrex IPR-12
 Pulse Rate: 2 sec
 August/97
 Current electrode is west of receiving electrodes (heading east)
 Mx Chargeability, 690-1050 msec after shutoff



LINE: 2050N

TEUTON RESOURCES CORP.
 MAIN GRID, CLONE PROJECT, STEWART AREA, B.C.
 LINE: 2000N
 INDUCED POLARIZATION SURVEY (Pole-Dipole Array)
 SCOTT GEOPHYSICS LTD.
 Scintrex IPR-12
 Pulse Rate: 2 sec
 August/97
 Current electrode is west of receiving electrodes (heading east)
 Mx Chargeability, 690-1050 msec after shutoff



LINE: 2000N

PART 2 OF 2


25,335

TEUTON RESOURCES CORP
 CAMP GRID, CLONE PROJECT
 STEWART AREA, B.C.
 CHARGEABILITY/RESISTIVITY
 PSEUDOSECTIONS
 L2000N-L2100N


DRAWN BY: jph DATE: August/97
 SCOTT GEOPHYSICS LTD.

(14)


TEUTON RESOURCES CORP.
 MAIN GRID, CLONE PROJECT, STEWART AREA, B.C.
 LINE: 2500N
 INDUCED POLARIZATION SURVEY (Pole-Dipole Array)
 SCOTT GEOPHYSICS LTD.
 Scintrex IPR-12
 Pulse Rate: 2 sec
 August/97
 Current electrode is east of receiving electrodes (heading west)
 Mx Chargeability, 680-1050 msec after shutoff




TEUTON RESOURCES CORP.
 MAIN GRID, CLONE PROJECT, STEWART AREA, B.C.
 LINE: 2450N
 INDUCED POLARIZATION SURVEY (Pole-Dipole Array)
 SCOTT GEOPHYSICS LTD.
 Scintrex IPR-12
 Pulse Rate: 2 sec
 August/97
 Current electrode is east of receiving electrodes (heading west)
 Mx Chargeability, 680-1050 msec after shutoff




TEUTON RESOURCES CORP.
 MAIN GRID, CLONE PROJECT, STEWART AREA, B.C.
 LINE: 2400N
 INDUCED POLARIZATION SURVEY (Pole-Dipole Array)
 SCOTT GEOPHYSICS LTD.
 Scintrex IPR-12
 Pulse Rate: 2 sec
 August/97
 Current electrode is east of receiving electrodes (heading west)
 Mx Chargeability, 680-1050 msec after shutoff



TEUTON RESOURCES CORP.
 MAIN GRID, CLONE PROJECT, STEWART AREA, B.C.
 LINE: 2350N
 INDUCED POLARIZATION SURVEY (Pole-Dipole Array)
 SCOTT GEOPHYSICS LTD.
 Scintrex IPR-12
 Pulse Rate: 2 sec
 August/97
 Current electrode is east of receiving electrodes (heading west)
 Mx Chargeability, 680-1050 msec after shutoff



TEUTON RESOURCES CORP.
 MAIN GRID, CLONE PROJECT, STEWART AREA, B.C.
 LINE: 2300N
 INDUCED POLARIZATION SURVEY (Pole-Dipole Array)
 SCOTT GEOPHYSICS LTD.
 Scintrex IPR-12
 Pulse Rate: 2 sec
 August/97
 Current electrode is east of receiving electrodes (heading west)
 Mx Chargeability, 680-1050 msec after shutoff




PART 2 OF 2
 GEOLOGICAL SURVEY BRANCH
 ASSESSMENT REPORT

25,335

TEUTON RESOURCES CORP.
 MAIN GRID, CLONE PROPERTY
 STEWART AREA, B.C.
 CHARGEABILITY/RESISTIVITY
 PSEUDOSECTIONS
 L2300N-L2500N

DRAWN BY: jph DATE: August/97
 SCOTT GEOPHYSICS LTD.




SURVEY SPECIFICATIONS

survey magnetometer	Scintrex MP4
base magnetometer	Scintrex IGS
type	proton
posted value units	total field gammas (nT)
contour interval	200 gammas

SURVEY BRANCH
 REPORT

25 335

PART 2 OF 2



TEUTON RESOURCES CORP.

C-1 GRID, CLONE PROJECT
 STEWART AREA, B.C.
 TOTAL FIELD MAGNETOMETER
 PLAN MAP

Contour Interval - 200 nT

DRAWN BY: jph DATE: August/97
 SCOTT GEOPHYSICS LTD.