APPENDIX VI

BC2K Diamond Drill Hole Logs / Assays

26604
2 of 3.

LEGEND

BC2K Drill Hole Lithology Codes:

Unit 1 = Bedded meta sandstone/meta siltstone, beds vary from laminae 5-20 cm wide pale to dark grey or black, pale beds are gritty, dark beds are fine grained. Graded bedding locally developed. Black beds are the minor component. (1a = light grey coloured equivalent)

Unit 2 = Finely laminated, often carbonaceous, dark grey to black meta siltstone/mudstone. Interbedded with other units.

Unit 3 = Grey laminated unit with alternating pale blue-grey, fine grained, translucent (watery) quartz bands and carbonaceous and sericite-rich lamina. (3a = light grey coloured equivalent)

Unit 4 = Coarse silver to green-grey muscovite schist. Possible alteration halo around mineralization or a tuff?

Unit 5 = Pale tan to grey, locally darker grey, sericite phyllite, characterized by disseminated magnetite, which is locally replaced by pyrite. Unit may also contain narrow localized dark green bands. Poorly laminated, but strongly foliated, generally homogeneous in appearance. May contain dolomite porphyroblasts. Hanging wall to BC vein. (5a = green coloured phyllite; 5b = magnetite porphyroblastic phyllite)

Unit 6 = Gritty blue-grey dolomitic rock, with variably coloured muscovite lamina.

Unit 7 = Laminated tan coloured phyllite. Tan phyllo-silicate lamina alternate with gritty, grey quartz±dolomite lamina, thin to thickly laminated. Similar/gradational to Unit 6. Possibly altered Unit 1. (7a = yellow and / or green coloured muscovite phyllite)

Unit 8 = Laminated tan coloured phyllite composed almost entirely of phyllo-silicate lamina, no gritty component. Gradational from Unit 7. Possibly altered Unit 2.

Unit 9 = Homogenous, massive competent, fine grained grey/purple/tan unit. Often with bundant pale yellowish siderite stringers, with or without pyrite and pyrrhotite. Distinctly mauve coloured muscovite component.

Unit 10 = White quartz veins, usually with yellow blocky carbonate, sometimes with pyrite mm to metre scale (BC vein).

f = fault

qs = quartz stringer

qv = quartz vein

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
BC2K-01							
	0.0	35.0	0	-	-	-	0
	35.0	40.0	3	-	f	-	0
	40.0	100.0	3	-	-	-	0.
	100.0	105.0	3	-	f	-	0.
	105.0	117.0	3	-	-	-	0.
	117.0	123.0	7	-	-	-	1
	123.0	125.3	1	-	-	-	0.
	125.3	152.3	1	-	-	qs	0.
	152.3	155.0	1	-	f	-	0.
	155.0	193.9	1	-	-	-	0.
	193.9	201.8	7	-	-	-	1
	201.8	225.0	1	-	-	-	0.
	225.0	234.6	4	-	-	-	3
	234.6	235.0	4	-	f	-	3
	235.0	237.3	1	-	-	-	0.
	237.3	240.0	7	-	f	-	3
	240.0	249.6	1	-	-	-	5
	249.6	250.0	1	-	f	-	0.
	250.0	256.0	1	-	-	-	0.
	256.0	261.0	8	-	-	-	0.
	261.0	270.0	1	-	-	qs	0.
	270.0	275.0	6	-	-	-	2
	275.0	289.0	1	-	-	-	0.
	289.0	300.0	4	-	-	-	2
	300.0	308.0	4	-	-	-	5
	308.0	315.0	1	-	-	-	0.
	315.0	330.6	1	-	f	-	0.
	330.6	331.0	1	-	f	-	0.
	331.0	350.0	1	-	-	qs	0.
BC2K-02							
	0.0	42.0	0	-	-	-	0
	42.0	61.0	1	-	-	-	0.
	61.0	130.2	1	-	-	-	0.
	130.2	131.5	10	-	-	qv	0.
	131.5	133.5	1	-	-	-	0.
	133.5	133.8	1	-	f	-	0.
	133.8	147.5	1	-	-	-	0.
	147.5	220.0	1	-	-	qs	0.
	220.0	250.0	6a	-	-	-	0.
BC2K-03							
	0.0	42.0	0	-	-	-	0
	42.0	45.0	0	-	-	-	0.
	45.0	50.5	5	-	-	-	0.
	50.5	75.0	5a	-	-	-	0.
	75.0	76.0	5a	-	f	-	0.
	76.0	80.0	5a	-	-	-	0.
	80.0	83.5	2	-	-	-	0.
	83.5	85.5	5	-	f	-	0.
	85.5	89.0	2	-	-	-	0.
	89.0	90.5	10	-	-	qv	0.
	90.5	98.0	2	-	f	-	2

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	98.0	110.5	10	-	-	qv	1
	110.5	114.5	2	-	-	-	3
	114.5	118.0	5	-	-	qs	0.
	118.0	125.0	2	-	-	-	2
	125.0	135.0	6	0.050	-	-	3
	135.0	142.0	6	0.312	-	-	3
	142.0	143.0	6	0.312	-	-	1
	143.0	145.0	6	0.312	-	-	3
	145.0	147.5	6	-	-	-	3
	147.5	151.0	2	-	-	-	0.
	151.0	159.0	3a	-	-	-	5
	159.0	162.0	3	-	f	-	5
	162.0	166.0	2	-	-	-	1
	166.0	169.2	3a	-	-	-	2
	169.2	170.1	3a	-	-	-	3
	170.1	172.5	3a	-	-	-	0.
	172.5	173.3	3a	-	-	-	0.
	173.3	180.6	4	-	-	-	5
	180.6	186.0	7	-	-	-	2
	186.0	187.0	7	-	-	-	4
	187.0	189.0	7	-	-	-	5
	189.0	190.0	7	-	f	-	5
	190.0	192.0	7	-	-	-	5
	192.0	196.0	4	-	-	-	5
	196.0	210.0	8	-	-	-	3
	210.0	214.5	8	0.098	-	-	3
	214.5	215.0	8	0.098	-	-	3
	215.0	219.0	8	0.098	-	-	7
	219.0	220.0	8	0.098	-	-	1
	220.0	223.0	8	0.098	-	-	2
	223.0	225.0	8	0.098	-	qs	2
	225.0	230.0	8	0.553	-	-	2
	230.0	234.5	8	0.553	f	-	5
	234.5	240.0	7	-	f	-	5
	240.0	250.0	7	-	-	-	5
BC2K-04							
	0.0	25.0	0	-	-	-	0
	25.0	55.5	5a	-	-	qs	0.
	55.5	99.9	5	-	-	-	0.
	99.5	112.0	2	-	-	-	0.
	112.0	113.0	2	-	-	qs	3
	113.0	114.0	2	-	-	-	0.
	114.0	119.8	2	-	-	-	3
	119.8	124.0	10	0.126	-	qv	2
	124.0	125.0	10	0.126	f	qs	2
	125.0	136.0	10	-	-	qv	2
	136.0	138.0	2	-	f	qv	2
	138.0	142.0	2	-	f	-	0.
	142.0	145.0	6	0.071	-	-	1
	145.0	160.0	6	0.512	-	-	1
	160.0	178.6	6	0.043	-	-	1
	178.6	200.0	2	-	-	-	0.
BC2K-05							

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	0.0	20.0	0	-	-	-	0
	20.0	40.0	0	-	-	-	0.1
	40.0	57.0	1	-	-	-	0.1
	57.0	107.5	1	-	-	-	0.1
	107.5	108.9	1	-	f	-	0.1
	108.9	140.0	6	-	-	-	0.1
	140.0	145.0	1	-	-	-	0.1
	145.0	148.0	10	-	-	qv	0.1
	148.0	149.0	2	-	-	-	0.1
	149.0	158.0	1	-	-	-	0.1
	158.0	200.0	1	-	-	-	2
BC2K-06							
	0.0	27.0	0	-	-	-	0
	27.0	75.0	10	-	-	qv	0.1
	75.0	83.7	2	-	-	-	0.1
	83.7	91.5	6	-	-	-	0.1
	91.5	95.0	1	-	-	-	0.1
	95.0	112.0	7	-	-	-	2
	112.0	113.6	7	-	-	-	10
	113.6	125.0	7a	-	-	-	0.1
BC2K-07							
	0.0	12.0	0	-	-	-	0
	12.0	26.0	0	-	-	-	0.1
	26.0	35.0	10	-	f	qv	10
	35.0	44.0	10	-	-	qv	10
	44.0	44.8	10	-	-	-	10
	44.8	85.0	10	-	-	qv	10
	85.0	88.5	2	-	-	-	1
	88.5	95.0	6	-	-	-	2
BC2K-08							
	0.0	20.0	0	-	-	-	0
	20.0	40.0	5b	-	-	-	0.1
	40.0	50.0	5a	-	-	-	0.1
	50.0	52.0	5a	0.095	-	qs	5
	52.0	55.5	5a	-	-	qs	5
	55.5	56.0	5a	-	f	-	0.1
	56.0	59.0	5a	-	-	qs	0.1
	59.0	62.5	10	-	f	qs	0.1
	62.5	65.0	10	-	-	qv	0.1
	65.0	69.0	10	-	-	qv	0.1
	69.0	70.0	10	-	f	-	0.1
	70.0	80.0	10	-	-	qv	0.1
	80.0	84.0	10	-	f	-	0.1
	84.0	86.0	10	-	f	-	0.1
	86.0	87.0	10	-	-	qv	0.1
	87.0	89.4	7	-	f	-	0.1
	89.4	94.5	7	-	-	-	2
	94.5	99.0	7	0.164	-	-	10
	99.0	105.0	7	0.164	-	qs	0.5
	105.0	110.0	7	0.164	-	-	10
	110.0	112.6	7	-	-	qs	0.1
	112.6	115.0	2	-	-	-	0.1

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	115.0	116.0	2	-	f	-	0.1
	116.0	123.5	2	-	-	-	0.1
	123.5	134.0	4	-	-	-	2
	134.0	140.8	10	-	-	qv	0.1
	140.8	153.0	4	-	-	-	5
	153.0	160.0	7	-	-	-	25
	160.0	164.8	7	0.053	-	-	25
	164.8	175.6	7	0.053	-	-	7
	175.6	178.9	10	-	-	qv	40
	178.9	179.1	7	-	f	-	0.1
	179.1	180.2	10	-	-	qv	0.1
	180.2	210.2	7	-	-	-	2
	210.2	221.8	7	0.419	-	-	60
	221.8	223.9	7	0.419	-	-	5
	223.9	228.9	2	0.419	-	qs	0.1
	228.9	242.8	2	-	-	qs	0.1
	242.8	305.0	3	-	-	-	0.1
BC2K-09							
	0.0	15.0	0	-	-	-	0
	15.0	19.0	0	-	-	-	0.1
	19.0	35.3	5b	-	-	-	0.1
	35.3	37.0	5b	-	-	-	2
	37.0	41.5	5b	-	-	-	0.1
	41.5	45.0	10	-	-	qv	0.1
	45.0	51.8	5b	-	-	-	0.1
	51.8	52.8	10	-	-	qv	0.1
	52.8	64.0	5b	-	-	-	0.1
	64.0	74.0	5	-	-	-	0.1
	74.0	75.0	5	-	f	-	0.1
	75.0	77.5	10	-	-	qv	0.1
	77.5	84.0	10	0.207	-	qv	15
	84.0	100.7	10	-	-	qv	0.1
	100.7	101.5	10	0.033	f	qs	0.1
	101.5	102.3	10	1.580	f	-	50
	102.3	106.4	6	0.042	-	qs	2
	106.4	113.1	6	0.042	-	-	35
	113.1	134.0	6	0.042	-	-	5
	134.0	149.6	4	-	-	-	7
	149.6	152.4	2	-	-	-	0.1
	152.4	160.8	7	-	-	-	1
	160.8	165.8	4	-	-	-	1
	165.8	167.0	2	-	-	-	7
	167.0	167.6	2	-	-	-	7
	167.6	172.6	2	-	-	-	7
	172.6	177.6	2	-	-	-	10
	177.6	178.6	2	-	-	-	0.1
	178.6	180.8	2	-	-	-	2
	180.8	198.2	2	-	-	-	3
	198.2	199.8	4	-	-	-	0.1
	199.8	205.0	2	-	-	-	5
	205.0	206.0	2	-	-	-	5
	206.0	207.0	2	-	f	-	5
	207.0	213.3	2	-	-	-	5
	213.3	230.2	2	-	-	-	3

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	230.2	236.7	4	-	-	-	1(
	236.7	245.7	7	-	-	-	2
	245.7	276.6	7	-	-	-	3(
	258.7	276.6	7	-	-	-	1(
	276.6	285.0	7	-	-	-	3
	285.0	296.0	7	-	-	-	3
	296.0	300.0	7	-	f	-	3
	300.0	315.8	7	-	-	-	5
	315.8	326.2	7	-	-	-	3
	326.2	333.4	7	-	-	-	1
	333.4	361.0	7	-	-	-	0.1
	361.0	395.0	7	-	-	-	0.1
BC2K-10							
	0.0	54.0	0	-	-	-	0
	54.0	65.0	0	-	-	-	0.1
	65.0	85.0	10	-	-	qv	0.1
	85.0	86.0	10	-	f	qv	0.1
	86.0	107.5	5	-	-	"	2
	107.5	112.6	6	-	-	"	2
	112.6	116.0	6	-	-	"	1
	116.0	155.6	6	-	-	"	0.1
	155.6	157.3	2	-	-	"	0.1
	157.3	157.9	4	-	-	"	0.1
	157.9	160.3	4	0.127	-	"	6.0
	160.3	166.4	7a	0.127	-	"	0.1
	166.4	177.3	7	0.127	-	"	0.1
	177.3	196.1	7	0.127	-	"	0.1
	196.1	200.2	7	1.205	-	"	20
	200.2	202.8	7	1.205	-	"	0.5
	202.8	211.5	7	1.205	-	"	55
	211.5	214.4	7	1.205	f	"	0.5
	214.4	215.0	7	1.205	-	"	50
	215.0	216.0	7	1.205	-	"	0.5
	216.0	221.0	7	1.205	-	"	0.5
	221.0	229.0	7	1.205	-	"	50
	229.0	230.0	7	1.205	-	"	0.5
	230.0	237.0	7	1.205	-	"	25
	237.0	240.6	7	1.205	-	"	0.5
	240.6	242.6	2	1.205	-	"	40
	242.6	250.8	2	-	f	"	10
	250.8	252.6	2	-	-	"	3
	252.6	255.3	2	-	-	qs	0.5
	255.3	259.0	7	-	-	"	3
	259.0	267.1	7	-	-	"	7
	267.1	270.6	3	-	-	"	5
	270.6	288.0	3a	-	-	"	5
	288.0	299.5	3a	-	-	qs	3
	299.5	300.1	3a	-	f	"	3
	300.1	305.0	4	0.060	-	-	0.5
	305.0	311.3	4	0.193	-	-	0.5
	311.3	312.4	4	0.193	-	-	50
	312.4	314.6	4	-	-	-	0.1
	314.6	315.4	10	-	-	qv	0.1
	315.4	320.0	4	-	-	-	0.1

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	320.0	322.0	4	0.061	f	-	7
	322.0	342.5	4	0.061	-	-	-
	342.5	343.4	3	0.061	-	-	30
	343.4	348.6	3	0.061	-	-	0.1
	348.6	350.0	3a	-	-	-	0.1
	350.0	359.0	3a	-	-	-	2
	359.0	361.2	4	0.035	-	-	30
	361.2	363.4	4	-	f	-	0.1
	363.4	375.7	2	-	-	qs	5
	275.7	379.7	2	-	-	-	3
	379.7	382.7	2	-	-	-	20
	382.7	387.0	2	-	-	qs	35
	387.5	388.0	2	-	f	-	0.1
	388.0	395.0	3	-	-	-	10
	395.0	400.0	3	-	-	-	0.1
BC2K-11							
	0.0	56.0	0	-	-	-	0
	56.0	60.0	10	0.028	-	qv	0.1
	60.0	65.0	5	-	-	-	0.1
	65.0	70.2	2	-	-	-	0.1
	70.2	73.0	10	-	-	qv	0.1
	73.0	80.0	10	-	f	qv	0.1
	80.0	96.0	10	-	-	qv	0.1
	96.0	98.0	2	-	-	-	0.1
	98.0	105.0	10	-	-	qv	0.1
	105.0	114.0	2	-	-	-	3
	114.0	127.8	6	-	-	-	0.1
	127.8	134.5	6	-	-	-	0.1
	140.0	154.6	6	-	-	-	5
	154.6	160.2	6	-	-	-	0.1
	160.2	165.0	6	-	-	-	2
	165.0	173.3	6	-	-	qs	0.1
	173.3	178.0	6	-	-	-	3
	178.0	181.9	6	-	-	-	5
	181.9	190.0	6	0.056	-	-	20
	190.0	197.6	6	0.221	-	-	40
	197.6	199.0	2	-	-	-	0.1
	199.0	201.0	2	-	-	-	5
	201.0	203.5	2	-	f	-	5
	203.5	208.0	2	-	-	-	5
	208.0	215.0	2	-	f	-	5
	215.0	245.7	2	-	-	-	5
	245.7	248.0	4	-	-	-	3
	248.0	254.5	7	-	-	-	5
	254.5	254.7	7	-	f	-	5
	254.7	259.6	9	-	-	-	20
	259.6	261.8	9	-	-	-	10
	261.8	275.0	9	-	-	-	3
	275.0	281.0	10	-	-	qv	2
	281.0	296.8	9	-	-	-	7
	296.8	305.8	9	-	-	-	1
	305.8	307.7	9	-	-	-	3
	307.7	309.3	9	-	-	-	20
	309.3	314.5	9	-	-	-	10

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	314.5	327.9	9	-	-	-	3
	327.9	329.2	9	-	f	-	0.
	329.2	343.8	9	-	-	-	0.
	343.8	357.9	7a	-	-	-	0.
	357.9	365.3	9	-	-	qs	0.
	365.3	393.0	9	-	-	-	0.
	393.0	434.3	9	-	-	-	2(
	434.3	454.0	9	-	-	-	5
	454.0	458.1	9	-	-	-	2(
	458.1	461.1	9	-	-	-	0.
	461.1	464.8	9	-	-	qs	0.
	464.8	484.5	9	-	-	-	0.
	473.5	484.5	9	-	-	-	2
	484.5	485.0	9	-	f	-	2
	485.0	505.0	9	-	-	-	2
BC2K-12							
	0.0	10.0	0	-	-	-	0
	10.0	55.0	2	-	-	-	0.1
	55.0	60.0	2	-	f	-	0.1
	60.0	66.4	2	-	-	-	0.1
	66.4	82.9	5b	-	-	-	0.1
	82.9	99.5	5a	-	-	-	0.1
	99.5	114.2	1	-	-	-	0.1
	114.2	118.0	2	-	-	-	0.1
	118.0	120.0	2	-	f	-	0.1
	120.0	123.0	2	-	-	-	0.1
	123.0	130.0	5	-	-	-	0.1
	130.0	131.0	5	-	f	-	0.1
	131.0	167.2	5	-	-	-	0.1
	167.2	175.0	10	-	-	qv	0.1
	175.0	176.0	2	-	f	-	0.1
	176.0	178.0	2	-	-	-	0.1
	178.0	179.0	10	-	-	qv	0.1
	179.0	182.5	2	-	f	-	0.1
	182.5	184.9	4	0.074	-	-	0.1
	184.9	186.6	4	0.074	-	-	3
	186.6	195.5	6	0.074	-	-	3
	195.5	197.5	6	-	-	-	3
	197.5	199.3	6	-	-	qs	3
	199.3	200.4	6	0.721	-	-	50
	200.4	204.6	6	0.721	-	qs	3
	204.6	207.0	6	0.721	-	-	50
	207.0	209.0	6	0.721	-	qv	3
	209.0	240.5	6	0.721	-	-	20
	240.5	242.2	6	-	-	-	7
	242.2	245.6	6	0.553	-	-	7
	245.6	252.6	4	0.025	-	-	3
	252.6	257.0	4	0.734	-	-	50
	257.0	264.8	4	0.028	-	-	0.5
	264.8	268.0	2	-	-	-	7
	268.0	270.0	2	-	f	-	0.1
	270.0	302.0	2	-	-	-	7
	302.0	305.0	2	-	f	-	0.1
	305.0	306.2	2	-	-	-	7

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	306.2	306.9	2	-	-	qv	0.
	306.9	311.0	2	-	-	-	0.
	311.0	317.5	2	-	-	-	7
	317.5	320.0	2	-	f	-	7
	320.0	325.0	2	-	-	-	7
	325.0	330.6	9	-	-	-	0.
	330.6	340.0	9	-	-	-	0.
	340.0	341.8	9	-	f	-	0.
	341.8	343.2	9	-	-	-	5
	343.2	346.5	9	-	f	-	0.
	346.5	348.0	9	-	-	-	2
	348.0	357.3	9	-	-	-	0.
	357.3	358.4	9	-	-	qs	0.
	358.4	359.0	9	-	f	-	0.
	359.0	362.6	9	-	-	qs	0.
	362.6	367.0	9	-	-	-	0.1
	367.0	370.0	9	-	f	-	0.1
	370.0	374.7	9	-	-	-	0.1
	374.7	376.2	10	-	-	qv	0.1
	376.2	392.5	9	-	-	qs	1
	392.5	465.0	9	-	-	-	0.1
BC2K-13							
	0.0	70.0	0	-	-	-	0
	70.0	85.0	5b	-	-	-	0.1
	85.0	107.3	5	-	-	-	0.1
	107.3	113.5	5a	-	-	-	0.1
	113.5	130.0	5b	-	-	-	0.1
	130.0	135.0	2	-	-	-	3
	135.0	138.2	4	-	-	-	0.1
	138.2	145.0	10	-	-	qv	0.1
	145.0	149.0	2	-	-	-	0.1
	149.0	152.0	10	-	-	qv	0.1
	152.0	163.0	4	-	-	qs	1
	163.0	165.0	10	-	f	-	3
	165.0	170.0	4	-	-	-	1
	170.0	180.0	6	-	-	-	1
	180.0	194.5	6	-	-	-	5
	194.5	200.0	6	-	-	-	5
	200.0	205.0	6	0.062	-	-	5
	205.0	210.0	6	-	-	-	5
	210.0	222.5	6	-	-	-	1
	222.5	226.0	6	-	-	-	3
	226.0	229.4	6	-	f	-	3
	229.4	233.4	2	-	-	-	1
	233.4	235.0	6	-	-	-	3
	235.0	240.0	2	-	-	-	1
	240.0	241.0	8	-	f	-	5
	241.0	245.0	8	-	-	-	25
	245.0	255.0	8	0.341	-	-	25
	255.0	260.0	8	0.054	-	-	25
	260.0	275.0	8	0.179	-	-	25
	275.0	280.0	8	-	-	-	25
	280.0	281.5	8	0.033	-	-	25
	281.5	283.5	8	0.794	-	-	20

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	283.5	293.5	8	0.794	-	-	10
	293.5	295.0	8	0.060	-	-	15
	295.0	300.7	8	0.520	-	-	15
	300.7	320.0	8	0.520	-	-	40
	320.0	332.0	8	0.137	-	-	40
	332.0	354.0	4	0.137	-	-	25
	354.0	359.0	4	-	-	-	15
	359.0	372.4	3	-	-	-	5
	372.4	382.6	2	-	-	-	10
	382.6	419.3	3	-	-	-	10
	419.3	425.0	3	-	f	-	1
	425.0	456.6	3	-	-	qs	0.1
	456.6	461.5	3a	-	-	qs	0.1
	461.5	467.5	3	-	-	qs	0.1
	467.5	482.8	3	-	f	qs	0.1
	482.8	485.0	3	-	-	qs	0.1
	485.0	495.0	3a	-	f	"	0.1
	495.0	500.9	3a	-	-	"	0.1
	500.9	501.4	3a	-	f	"	0.1
	501.4	530.0	2	-	-	"	1
	530.0	535.0	2	-	f	-	0.1
	535.0	537.7	2	-	f	-	0.1
	537.7	600.0	1	-	-	-	0.1
BC2K-14							
	0.0	40.0	0	-	-	-	0
	40.0	50.0	5b	-	-	-	0.1
	50.0	53.5	5b	-	f	-	0.1
	53.5	100.0	5b	-	-	-	0.1
	85.0	90.0	5b	-	f	-	0.1
	90.0	100.0	5b	-	-	-	0.1
	100.0	102.2	10	-	-	qv	0.1
	102.2	105.0	5b	-	-	-	0.1
	105.0	113.0	5b	-	-	qs	5
	113.0	114.3	5b	-	-	-	0.1
	114.3	127.0	2	-	-	-	0.1
	127.0	130.0	5	-	-	-	0.1
	130.0	139.0	5	-	-	qs	10
	139.0	152.6	5	-	-	-	0.1
	152.6	156.3	2	-	-	-	0.1
	156.3	165.3	5	-	-	-	0.1
	165.3	169.7	2	-	f	-	5
	169.7	170.0	10	-	-	qv	5
	170.0	194.2	4	-	-	qs	5
	194.2	194.6	2	-	f	-	5
	194.6	206.0	1	-	-	-	1
	206.0	208.0	2	-	-	-	1
	208.0	210.0	1	-	-	-	1
	210.0	215.7	2	-	-	-	1
	215.7	218.3	6	-	-	-	0.1
	218.3	221.5	6	-	-	-	2
	221.5	230.0	6	-	-	-	3
	230.0	236.0	6	-	-	-	3
	236.0	251.5	6	-	-	-	1
	251.5	265.0	6	-	-	-	0.1

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	265.0	276.5	4	-	-	-	5
	276.5	283.3	7	-	-	-	5
	283.3	286.6	7	-	f	-	0.1
	286.6	290.0	7	-	-	-	5
	290.0	295.0	7	0.049	-	-	5
	295.0	315.0	7	-	-	-	15
	315.0	344.5	9	-	-	-	1
	344.5	353.0	9	0.168	-	-	15
	353.0	355.0	4	0.168	-	-	15
	355.0	358.0	4	-	-	-	15
	358.0	360.0	9	-	-	-	15
	360.0	365.0	9	0.025	-	-	15
	365.0	390.0	9	0.079	-	-	15
	390.0	410.0	9	-	-	-	15
	410.0	435.0	9	-	-	-	25
	412.5	413.8	9	0.125	-	-	50
	413.8	424.3	9	-	-	-	15
	424.3	426.4	9	0.126	-	-	50
	426.4	432.2	9	-	-	-	15
	432.2	433.7	9	0.070	-	-	50
	433.7	437.5	9	-	-	-	15
	437.5	440.2	3	-	-	qs	5
	440.2	443.0	4	-	-	"	20
	443.0	455.0	3	-	-	"	5
	444.5	448.2	3a	-	-	qs	10
	448.2	455.0	3	-	-	"	5
	455.0	456.5	4	-	-	"	20
	456.5	461.0	3	-	-	"	5
	461.0	465.5	4	-	-	"	20
	465.5	470.0	4	-	f	"	-
	470.0	475.0	3	-	-	"	5
	475.0	485.0	3	-	f	"	5
	485.0	490.0	3	-	-	qs	5
	490.0	496.0	3	-	f	qs	0.1
	496.0	555.0	1	-	-	qs	0.1
	542.7	544.0	1	-	-	qs	0.1
	544.0	555.0	1	-	-	qs	0.1
BC2K-15							
	0.0	74.0	0	-	-	-	0
	74.0	78.8	5b	-	-	-	0.1
	78.8	79.4	10	-	-	qv	3
	79.4	108.5	5b	-	-	-	0.1
	108.5	109.4	10	-	-	qv	2
	109.4	114.0	5b	-	-	-	0.1
	114.0	120.0	5b	-	f	qs	0.1
	120.0	123.4	5b	-	-	-	0.1
	123.4	132.0	2	-	-	-	0.1
	132.0	171.0	5b	-	-	-	0.1
	171.0	182.4	5	-	-	-	0.1
	182.4	183.5	2	-	-	-	1
	183.5	184.6	10	-	-	-	1
	184.6	194.8	2	-	f	qs	1
	194.8	200.0	2	-	-	qs	1
	200.0	201.0	2	0.366	-	qs	1

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	201.0	202.2	10	0.366	-	qv	15
	202.2	205.0	2	0.366	-	qs	1
	205.0	207.0	2	0.366	-	qs	1
	207.0	207.8	10	0.366	-	qv	1
	207.8	210.0	2	0.366	-	qs	1
	210.0	215.0	2	0.366	-	qs	1
	215.0	218.3	2	-	-	qs	1
	218.3	225.4	4	-	-	qs	1
	225.4	231.0	2	-	f	qs	1
	231.0	234.4	2	-	-	-	1
	234.4	248.0	6	-	-	-	1
	248.0	250.0	6	-	-	-	2
	250.0	252.1	6	-	-	-	5
	252.1	259.0	6	-	-	-	2
	259.0	262.0	6	0.032	-	-	5
	262.0	265.0	6	0.032	-	qs	3
	265.0	265.9	6	-	-	qs	3
	265.9	285.0	6	-	-	-	5
	285.0	286.0	6	-	-	-	3
	286.0	289.6	6	-	-	-	2
	289.6	300.5	6	-	-	-	5
	300.5	303.1	4	-	-	-	'
	303.1	327.0	2	-	-	-	.
	327.0	330.3	2	-	-	-	'
	330.3	340.9	7a	-	-	-	'
	340.9	342.2	7a	-	f	-	.
	342.2	347.0	7a	-	-	-	'
	347.0	379.2	7	-	-	-	.
	379.2	380.0	7	-	-	-	5
	380.0	385.0	7	0.031	-	-	5
	385.0	388.0	7	-	-	-	5
	388.0	410.0	7	-	-	-	1
	410.0	411.8	7	-	f	-	1
	411.8	414.7	7	-	-	-	1
	414.7	415.0	7	-	-	-	50
	415.0	416.1	7	-	-	-	1
	416.1	423.0	7	-	-	-	1
	423.0	441.5	7	-	-	-	5
	441.5	451.0	7	-	-	-	3
	451.0	466.1	7	-	-	-	2
	466.1	467.1	2	-	-	-	1
	467.1	470.2	7	-	-	-	1
	470.2	470.6	10	-	-	qv	1
	470.6	471.7	3	-	-	-	2
	471.7	472.1	10	-	-	qv	0.1
	472.1	499.7	3	-	-	-	2
	499.7	501.7	3	-	-	-	0.1
	501.7	515.0	3	-	-	-	2
	515.0	520.8	2	-	-	-	2
	520.8	526.0	3	-	-	-	2
	526.0	528.5	3	-	f	-	2
	528.5	534.1	1	-	-	-	2
	534.1	535.0	1	-	f	-	2
	535.0	550.1	1	-	-	-	1
	550.1	550.6	10	-	-	qv	1

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	550.6	605.0	1	-	-	-	1
BC2K-16							
	0.0	20.0	0	-	-	-	0
	20.0	30.0	10	-	f	qv	0.1
	30.0	75.0	10	-	-	qv	0.1
	75.0	80.1	10	-	f	qv	0.1
	80.1	85.0	10	-	f	qv	0.1
	85.0	101.0	6	-	-	-	0.1
	101.0	118.0	6	-	-	-	2
	118.0	135.0	6	-	-	-	0.1
	135.0	141.5	6	-	-	-	2
	141.5	147.0	2	-	-	-	3
	147.0	165.5	6	-	-	-	0.1
	165.5	169.0	2	-	f	-	1
	169.0	178.0	4	-	-	-	4
	178.0	189.5	2	-	-	-	1
	189.5	193.0	7	-	-	-	8
	193.0	200.0	2	-	-	-	1
	200.0	205.1	2	-	f	-	1
	205.1	214.9	3a	-	-	-	2
	214.9	238.0	7	-	-	-	3
	238.0	243.5	7	-	-	-	10
	243.5	245.6	7a	-	-	-	3
	245.6	250.0	7a	-	-	-	10
	250.0	263.5	3a	-	-	-	1
	263.5	272.6	3a	-	-	-	2
	272.6	274.1	3a	-	-	qs	1
	274.1	274.5	3	-	-	qs	0.1
	274.5	275.0	1	-	f	-	5
	275.0	306.0	1	-	-	qs	0.1
	306.0	329.4	1	-	-	-	0.1
	329.4	360.0	1	-	-	qs	0.1
	360.0	369.0	1	-	-	-	0.1
	369.0	370.0	1	-	f	-	0.1
	370.0	379.0	1	-	-	-	0.1
	379.0	380.8	10	-	f	qv	0.1
	380.8	400.0	1	-	-	-	0.1
	400.0	435.0	1	-	-	-	0.1
	435.0	440.0	2	-	-	qs	2
	440.0	443.6	10	0.413	-	qv	25
	443.6	479.0	3a	-	-	-	0.1
	479.0	480.0	10	-	-	qv	1
	480.0	526.3	1	-	-	-	1
	526.3	528.3	1	-	-	qs	1
	528.3	529.0	10	-	-	qv	1
	529.0	575.0	1	-	-	-	1
BC2K-17							
	0.0	30.0	0	-	-	-	0
	30.0	35.0	10	-	-	qv	0.1
	35.0	51.0	10	-	-	qv	0.1
	51.0	89.4	10	-	-	qv	0.1
	89.4	90.0	10	-	f	qs	0.1
	90.0	90.6	6	-	-	-	0.1

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	90.6	95.0	6	-	f	-	0.1
	95.0	101.5	6	-	-	-	0.1
	101.5	107.6	6	-	-	-	0.1
	107.6	112.3	6	-	-	-	1
	112.3	113.6	6	-	-	qs	3
	113.6	125.0	6	-	-	-	1
	125.0	134.0	6	-	-	-	0.1
	134.0	141.8	6	-	-	-	2
	141.8	150.6	3a	-	-	-	0.1
	150.6	158.5	3	-	-	-	0.1
	158.5	166.0	3a	-	-	-	0.1
	166.0	166.8	3	-	-	-	0.1
	166.8	174.5	3	-	-	-	1
	174.5	181.9	3	-	-	-	1
	181.9	190.6	3	-	-	-	0.1
	190.6	204.0	3a	-	-	-	5
	204.0	209.6	3	-	-	-	0.1
	209.6	214.5	3	-	f	-	0.1
	214.5	219.8	4	-	-	-	0.1
	219.8	229.5	7	-	-	-	2
	229.5	236.0	3	-	-	-	0.1
	236.0	240.0	7a	-	-	-	1
	240.0	289.4	8	-	-	-	3
	289.4	297.2	7a	-	-	-	2
	297.2	305.4	8	-	-	-	2
	305.4	320.0	8	-	-	-	0.1
	320.0	329.6	7	-	-	-	0.1
	329.6	334.6	7a	-	-	-	0.1
	334.6	339.5	7	-	-	-	1
	339.5	348.0	7a	-	-	-	2
	348.0	371.2	7	-	-	-	3
	371.2	372.2	7	-	f	-	3
	372.2	397.0	9	-	-	-	3
	397.0	398.2	9	-	-	-	10
	398.2	403.0	9	-	-	-	3
	403.0	403.9	9	-	-	-	25
	403.9	448.1	9	-	-	-	3
	448.1	456.1	9	-	-	-	15
	456.1	465.0	9	-	-	-	3
	465.0	471.6	9	-	-	-	15
	471.6	515.2	9	-	-	-	5
	515.2	520.0	9	-	-	-	20
	520.0	521.6	9	-	-	-	50
	521.6	526.4	9	-	-	-	5
	526.4	543.8	9	-	-	-	3
	543.8	549.0	9	-	-	-	5
	549.0	575.0	9	-	-	-	3
BC2K-18							
	0.0	26.0	0	-	-	-	0
	26.0	33.4	5	-	-	-	0.1
	33.4	34.5	5	-	f	-	0.1
	34.5	49.4	5	-	-	-	0.1
	49.4	50.0	5	-	f	-	0.1
	50.0	54.5	5	-	-	-	0.1

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%
	54.5	56.0	10	-	-	qv	0.
	56.0	65.0	5	-	-	-	0.
	65.0	66.3	10	0.025	-	qv	0.
	66.3	67.4	5	0.025	-	-	0.
	67.4	67.9	10	0.025	-	qv	0.
	67.9	68.3	5	0.025	-	-	0.
	68.3	70.0	5	0.025	f	-	0.
	70.0	70.5	5	-	-	-	0.
	70.5	77.5	10	-	-	qv	0.
	77.5	86.0	5	-	-	-	0.
	86.0	102.0	5	-	-	qs	0.
	102.0	106.4	5b	-	-	-	0.
	106.4	110.0	5b	-	-	qs	7
	110.0	114.3	5b	0.026	-	qs	7
	114.3	120.5	5b	-	-	qs	7
	120.5	137.2	5b	-	-	-	0.
	137.2	137.5	5b	-	-	-	1(
	137.5	153.7	5b	-	-	-	0.
	153.7	164.3	2	-	-	-	1
	164.3	165.0	10	-	f	qs	1
	165.0	169.5	2	-	-	-	1
	169.5	170.8	10	-	f	qs	1
	170.8	174.9	2	-	-	-	1
	174.9	175.7	2	-	-	qs	1
	175.7	200.0	2	-	-	-	1
	200.0	201.2	10	0.050	f	qs	2
	201.2	205.0	10	0.050	-	qv	0.
	205.0	212.9	10	-	-	qv	0.
	212.9	213.7	4	-	-	-	4
	213.7	258.7	10	-	-	qv	0.
	258.7	260.0	2	-	-	-	0.
	260.0	268.1	10	-	-	qv	3
	268.1	285.2	4	-	-	-	2
	282.0	282.5	2	-	f	qs	0.
	285.2	300.0	2	-	-	qs	5
	300.0	300.8	2	-	f	-	0.
	300.8	311.8	2	-	-	-	2
	311.8	327.3	6	-	-	-	0.
	312.4	313.2	6	-	f	-	0.
	313.2	316.8	6	-	-	-	0.
	316.8	319.5	2	-	f	qs	0.
	319.5	327.3	6	-	f	-	0.
	327.3	338.8	6	-	f	-	0.
	338.8	344.5	9	-	f	-	0.
	344.5	374.8	9	-	-	-	1
	374.8	393.0	9	-	-	-	0.
	393.0	394.1	10	-	-	qv	1(
	394.1	409.0	1	-	-	-	1
	409.0	415.0	1	-	-	-	0.
	415.0	425.0	1	-	-	qs	2
	425.0	430.0	1	0.032	-	-	0.
	430.0	465.1	1	-	-	-	0.
	465.1	474.3	7a	-	-	-	0.
	474.3	489.8	9	-	-	-	1(
	489.8	490.0	9	-	-	-	0.

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	490.0	500.0	9	-	-	-	0.1
	500.0	502.2	9	-	-	-	0.1
	502.2	506.0	9	-	-	-	0.1
	506.0	533.0	9	-	-	-	15
	533.0	565.0	9	-	-	-	0.1
	565.0	570.0	9	0.043	-	-	0.1
	570.0	603.0	9	-	-	-	0.1
	603.0	640.0	9	-	-	-	15
	640.0	675.5	9	-	-	-	0.1
	675.5	687.0	9	-	-	qs	0.1
	687.0	695.6	9	-	-	qs	0.1
	695.6	698.5	7a	-	-	qs	2
	698.5	714.7	2	-	-	qs	0.1
	714.7	725.4	4	-	-	-	0.1
	725.4	737.2	4	-	-	qs	10
	737.2	743.7	2	-	-	qs	5
	743.7	744.5	2	-	f	-	0.1
	744.7	800.0	1	-	-	qs	0.1
	747.1	747.6	10	-	-	qv	0.1
	747.6	800.0	1	-	-	qs	0.1
BC2K-19							
	0.0	52.0	0	-	-	-	0
	52.0	57.0	0	-	-	-	0.1
	57.0	59.0	5a	-	-	-	0.1
	59.0	85.0	5b	-	-	-	0.1
	85.0	91.5	5b	-	-	-	1
	91.5	96.8	5	0.060	-	-	1
	96.8	100.9	5	0.060	-	-	1
	100.9	101.3	2	0.060	-	-	1
	101.3	102.3	2	-	-	-	1
	102.3	111.1	5	-	-	-	1
	111.1	112.5	2	-	f	-	1
	112.5	127.8	5	-	-	-	1
	127.8	136.0	2	-	f	-	1
	136.0	138.5	4	-	-	-	1
	138.5	150.2	6	-	-	-	1
	150.2	152.4	2	-	-	-	1
	152.4	155.0	6	-	-	-	0.1
	155.0	155.8	2	-	-	-	1
	155.8	156.6	6	-	-	-	0.1
	156.6	158.5	2	-	-	-	1
	158.5	160.5	6	-	-	-	0.1
	160.5	162.7	2	-	-	-	1
	160.8	161.8	2	-	f	-	0.1
	161.8	162.7	2	-	-	-	1
	162.7	172.6	4	-	-	-	0.1
	172.6	181.0	6	-	-	-	0.1
	181.0	198.0	6	-	-	-	3
	198.0	221.0	6	-	-	-	0.1
	221.0	225.0	7	-	-	-	5
	225.0	230.0	7	0.030	-	-	5
	230.0	235.0	6	-	-	-	3
	235.0	245.2	3	-	-	-	2
	245.2	246.2	3a	-	-	-	2

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	246.2	247.0	3	-	-	-	2
	247.0	250.0	3a	-	-	qs	2
	250.0	253.0	2	-	-	-	2
	253.0	253.5	2	-	f	-	2
	253.5	258.0	2	-	-	-	2
	258.0	261.8	2	-	-	-	1
	261.8	268.0	7a	0.040	-	-	5
	268.0	270.0	7	0.529	-	-	5(
	270.0	274.9	7	0.529	-	-	1(
	274.9	275.5	7	0.529	-	-	5(
	275.5	280.0	7	0.529	-	-	1(
	280.0	285.0	7	0.529	-	-	1(
	285.0	291.4	7	0.529	-	-	1(
	291.4	293.0	7	0.529	-	-	5(
	293.0	296.1	7	0.529	-	-	1(
	296.1	298.8	7	0.529	-	-	5(
	298.8	300.0	7	0.529	-	-	1(
	300.0	308.8	4	0.529	f	-	3
	308.8	310.0	4	0.529	-	-	5(
	310.0	315.0	4	0.529	-	-	2(
	315.0	315.8	4	0.529	-	-	5(
	315.8	321.0	4	0.529	-	-	2(
	321.0	322.0	4	0.529	-	-	5(
	322.0	326.0	4	0.529	-	-	2(
	326.0	332.8	4	0.529	-	-	2(
	332.8	337.0	7	-	-	-	0.5
	337.0	351.7	6a	-	-	-	0.5
	351.7	362.5	6	-	-	-	5
	362.5	366.6	6	0.203	-	-	5(
	366.6	369.3	6	-	-	-	0.1
	369.3	372.0	4	0.039	-	-	1(
	372.0	373.0	4	0.039	-	-	5(
	373.0	374.0	4	0.039	-	-	1(
	374.0	380.2	2	0.025	-	"	1(
	380.2	387.0	2	-	-	"	1(
	387.0	388.0	2	-	f	qs	0.1
	388.0	391.7	2	-	-	"	0.1
	391.7	392.5	2	0.036	-	"	5(
	392.5	401.7	2	-	-	"	0.1
	401.7	402.4	2	-	f	"	0.1
	402.4	424.6	2	-	-	"	0.1
	424.6	439.9	7	-	-	"	1(
	439.9	440.7	10	-	-	qv	1(
	440.7	442.7	1	-	-	"	1(
	442.7	463.4	2	-	-	"	5
	463.4	483.6	1	-	-	"	3
	483.6	484.3	10	-	-	qv	0.1
	484.3	500.0	1	-	-	"	3
BC2K-20							
	0.0	34.0	0	-	-	-	(
	34.0	39.0	5b	-	-	"	0.1
	39.0	44.9	5a	-	-	"	0.1
	44.9	49.5	5b	-	-	"	0.1
	49.5	50.0	5b	-	f	"	0.1

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	50.0	53.0	5b	-	-	-	0.1
	53.0	55.2	5b	-	-	-	0.1
	55.2	63.0	5b	-	-	-	0.1
	63.0	63.7	5b	-	f	-	0.1
	63.7	71.5	5b	-	-	-	0.1
	71.5	80.6	5b	-	-	qs	0.1
	80.6	81.0	10	-	-	qv	0.1
	81.0	85.8	5b	-	-	qs	0.1
	85.8	86.4	10	-	-	qv	0.1
	86.4	88.8	5b	-	-	qs	0.1
	88.8	89.3	10	-	-	qv	0.1
	89.3	94.4	5b	-	-	-	0.1
	94.4	96.5	10	-	-	qv	5
	96.5	103.3	5	-	-	-	0.1
	103.3	106.7	5	-	-	qs	0.1
	106.7	112.0	5	-	-	-	0.1
	112.0	119.0	2	-	-	-	0.1
	119.0	120.1	2	-	-	-	0.1
	120.1	120.5	10	-	-	qv	0.1
	120.5	127.0	5	-	-	-	0.1
	127.0	127.9	5	-	-	-	0.1
	127.9	132.0	5	-	-	-	0.1
	132.0	141.5	5	-	-	-	0.1
	141.5	174.5	5	-	-	-	0.1
	174.5	195.1	2	-	-	-	1
	195.1	206.9	2	-	-	-	1
	206.9	208.9	2	-	-	qs	1
	208.9	209.3	2	-	f	-	1
	209.3	215.3	2	-	-	qs	-
	215.3	225.8	6	-	-	-	5
	221.0	225.0	6	0.057	-	-	5
	225.0	225.8	6	-	-	-	5
	225.8	261.6	6	-	-	-	2
	240.0	250.0	6	0.037	-	-	0.1
	250.0	260.0	6	-	-	-	0.1
	260.0	261.6	6	0.101	-	-	0.1
	261.6	265.0	6	0.101	-	-	3
	265.0	270.0	6	0.037	-	-	3
	270.0	274.5	6	-	-	-	3
	274.5	276.6	6	0.123	-	-	3
	276.6	276.8	6	0.123	f	-	15
	276.8	278.0	6	0.123	-	-	15
	278.0	286.0	6	-	-	-	2
	286.0	289.0	6	-	-	-	3
	289.0	290.7	6	0.233	-	-	15
	290.7	292.0	6	0.233	-	-	0.1
	292.0	295.5	6	-	-	-	0.1
	295.5	296.5	4	-	-	-	0.1
	296.5	301.5	4	-	-	-	3
	301.5	303.8	2	-	-	-	0.1
	303.8	304.2	2	-	f	-	0.1
	304.2	315.2	2	-	-	-	0.1
	315.2	315.9	2	-	f	-	0.1
	315.9	319.9	7	-	-	-	0.1
	319.9	320.4	7	-	f	-	0.1

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	320.4	329.8	7	-	f	-	0.1
	329.8	332.0	7	-	f	-	0.1
	332.0	353.6	9	-	-	-	1
	353.6	354.0	9	-	f	-	1
	354.0	362.5	9	-	-	-	1
	362.5	362.8	10	-	-	qv	1
	362.8	364.4	9	-	-	-	1
	364.4	369.0	9	-	f	-	4
	369.0	376.5	9	-	-	-	1
	376.5	379.7	9	-	-	-	1
	379.7	391.0	9	-	-	-	1
	391.0	393.4	9	-	f	-	1
	393.4	393.9	9	-	-	-	50
	393.9	400.0	9	-	-	-	1
	400.0	425.6	9	-	-	-	2
	425.6	427.5	9	-	-	-	8
	427.5	429.2	9	-	f	-	8
	429.2	443.0	9	-	-	-	8
	443.0	447.6	9	-	-	-	2(
	447.6	453.0	4	-	-	-	1
	453.0	468.9	2	-	-	-	3
	468.9	470.8	3	-	-	-	2
	470.8	476.2	3	-	-	-	0.1
	476.2	476.8	3	-	-	-	1
	476.8	501.9	3	-	-	-	0.1
	501.9	502.1	3	-	f	-	0.1
	502.1	509.6	3	-	-	-	0.1
	509.6	511.3	4	-	-	-	1
	511.3	512.5	3	-	f	-	0.1
	512.5	515.3	3	-	-	-	1
	515.3	515.7	3	-	f	-	0.1
	515.7	528.0	3	-	-	-	0.1
	528.0	538.3	3	-	-	-	0.1
	538.3	540.0	3	-	f	-	5
BC2K-21							
	0.0	24.0	0	-	-	-	(
	24.0	30.0	5	-	-	-	0.5
	30.0	32.6	5	-	-	-	0.5
	32.6	34.5	10	-	-	qv	2
	34.5	37.0	5	-	-	-	0.5
	37.0	38.0	5	-	-	-	0.5
	38.0	50.0	5	-	-	-	0.5
	50.0	50.6	10	-	f	qv	0.5
	50.6	60.6	10	-	-	qv	0.5
	60.6	73.7	10	-	-	qv	0.5
	73.7	75.0	10	-	-	qv	0.5
	75.0	75.2	10	-	f	qv	0.5
	75.2	80.0	10	-	-	qv	0.5
	80.0	81.2	2	-	-	-	0.5
	81.2	82.4	6	-	f	-	0.5
	82.4	83.1	6	-	-	-	0.5
	83.1	85.2	6	-	-	-	0.5
	85.2	113.0	6	-	-	qs	0.5
	113.0	115.8	10	-	-	qv	0.5

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	115.8	127.0	6	-	-	qs	0.5
	127.0	130.0	6	-	f	-	0.5
	130.0	133.0	2	-	-	-	1
	133.0	141.0	3	-	-	-	2
	141.0	148.3	3	-	-	qs	10
	148.3	157.2	3	-	-	-	2
	157.2	161.5	7	-	-	-	15
	161.5	170.0	7a	-	-	-	1
	170.0	177.6	9	-	-	-	4
	177.6	178.1	10	-	-	qv	4
	178.1	193.5	9	-	-	-	4
	193.5	200.4	9	-	-	-	7
	200.4	200.6	9	-	f	-	5
	200.6	230.2	9	-	-	-	2
	230.2	239.0	9	-	-	-	2
	239.0	242.8	9	-	-	-	2
	242.8	250.5	3a	-	-	qs	3
	250.5	253.4	2	-	-	-	3
	253.4	254.5	2	0.036	-	qs	3
	254.5	256.4	2	0.036	-	qs	10
	256.4	260.0	2	-	-	-	0.1
	260.0	267.7	2	-	-	-	0.1
	267.7	320.0	1	-	-	-	0.1
BC2K-22							
	0.0	18.0	0	-	-	-	0
	18.0	20.0	5	-	-	-	1
	20.0	36.5	5	0.028	-	-	1
	36.5	38.3	10	0.028	-	qv	15
	38.3	40.5	5	-	-	-	1
	40.5	41.5	10	-	-	qv	2
	41.5	50.6	5	-	-	-	1
	50.6	51.8	5	-	-	qs	1
	51.8	52.4	5	-	-	-	1
	52.4	53.2	10	0.035	f	qv	1
	53.2	54.8	10	0.035	-	-	15
	54.8	56.8	10	0.035	-	-	1
	56.8	61.7	10	0.035	-	-	1
	61.7	80.0	10	0.035	-	-	10
	80.0	86.5	10	-	f	qv	2
	86.5	89.5	6	-	-	-	2
	89.5	97.1	6	-	-	-	2
	97.1	98.8	10	-	-	qv	2
	98.8	100.0	6	-	-	-	2
	100.0	120.0	6	-	-	-	1
	120.0	123.2	6	-	-	-	1
	123.2	128.6	6	-	-	-	5
	128.6	135.3	6	-	-	-	1
	135.3	138.4	6	-	-	-	1
	138.4	149.5	2	-	f	qs	1
	149.5	149.7	10	-	-	qv	3
	149.7	160.0	3	-	-	-	1
	160.0	171.0	4	-	-	-	1
	171.0	174.8	7a	-	-	-	1
	174.8	183.3	7	-	-	-	25

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	183.3	188.0	7	-	-	-	1
	188.0	189.0	7	-	-	-	25
	189.0	207.5	7	-	-	-	5
	207.5	217.2	3	-	-	-	1
	217.2	220.0	7a	-	-	-	5
	220.0	223.0	7	-	-	-	5
	223.0	223.9	7	-	-	-	30
	223.9	225.5	7	-	-	-	5
	225.5	227.5	7	-	-	qs	5
	227.5	231.8	7	-	-	-	5
	231.8	250.0	9	-	-	-	3
	250.0	250.7	9	-	-	-	20
	250.7	255.5	9	-	-	-	3
	255.5	256.2	9	-	-	-	30
	256.2	266.2	9	-	-	-	3
	266.2	266.6	9	-	-	-	30
	266.6	268.5	9	-	-	-	3
	268.5	272.0	9	-	-	-	15
	272.0	282.7	9	-	-	-	3
	282.7	283.5	9	-	-	-	20
	283.5	288.5	9	-	-	-	3
	288.5	289.8	9	-	-	-	60
	289.8	295.5	9	-	-	-	3
	295.5	298.6	9	-	-	-	15
	298.6	306.0	9	-	-	-	3
	306.0	334.5	3	-	-	-	1
	334.5	354.0	9	-	-	-	1
	354.0	354.5	9	-	-	-	20
	354.5	357.4	9	-	-	-	1
	357.4	360.0	9	-	-	-	20
	360.0	362.5	9	-	-	-	1
	362.5	370.0	9	-	-	-	15
	370.0	370.4	9	-	-	-	1
	370.4	372.1	9	-	-	-	50
	372.1	379.6	9	-	-	-	1
	379.6	380.8	9	-	-	-	30
	380.8	390.0	9	-	-	-	1
BC2K23							
	0.0	56.0	0	-	-	-	0
	56.0	75.0	3	-	-	qs	4
	75.0	85.0	3	-	-	qs	3
	85.0	95.0	2	-	f	-	3
	95.0	96.3	10	-	f	qv	2
	96.3	119.4	2	-	f	-	3
	119.4	120.9	2	-	f	qs	3
	120.9	125.5	2	-	-	-	3
	125.5	146.4	3a	-	f	qs	1
	146.4	183.0	1	-	-	-	1
	183.0	185.8	1	-	f	-	1
	185.8	198.1	9	-	-	-	1
	198.1	216.0	1	-	-	-	1
	216.0	220.8	1	-	-	qs	1
	220.8	237.0	1	-	-	-	1
	237.0	238.7	1	-	f	-	1

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	238.7	252.6	1	-	-	-	1
	252.6	253.0	1	-	f	-	1
	253.0	268.2	1	-	-	-	1
	268.2	272.8	2	-	-	-	3
	272.8	273.9	2	-	-	qs	3
	273.9	276.8	2	-	-	-	3
	276.8	280.2	10	-	-	qv	2
	280.2	282.0	1	-	-	qs	0.5
	282.0	286.0	1	-	-	qs	0.5
	286.0	297.0	1a	-	-	qs	0.5
	297.0	405.0	1	-	-	-	0.5
BC2K24							
	0.0	29.0	0	-	-	-	0
	29.0	44.0	6	0.070	-	qs	5
	44.0	49.5	4	-	-	-	1
	49.5	56.4	4	0.259	-	-	10
	56.4	57.0	4	0.259	f	-	5
	57.0	77.0	9	-	-	-	0.1
	77.0	92.0	7	-	-	-	10
	92.0	97.5	7a	-	-	-	5
	97.5	104.0	9	-	-	-	25
	104.0	109.0	7a	-	-	-	5
	109.0	132.0	7	-	-	-	5
	132.0	134.5	7	-	-	qs	5
	134.5	142.0	7	-	-	-	5
	142.0	151.0	9	0.081	-	-	5
	151.0	155.0	7a	0.081	-	-	1
	155.0	160.3	9	-	-	-	2
	160.3	166.8	7a	-	-	-	2
	166.8	172.0	9	-	-	-	5
	172.0	178.0	9	0.044	-	-	5
	178.0	186.5	9	0.044	-	-	10
	186.5	191.0	9	-	-	-	5
	191.0	197.0	7	0.203	-	-	10
	197.0	202.0	7	0.027	-	-	10
	202.0	232.0	9	-	-	-	0.5
	232.0	242.0	9	0.046	-	-	0.5
	242.0	246.5	9	-	-	-	0.5
	246.5	247.5	9	-	-	qs	0.5
	247.5	256.0	9	-	-	-	0.5
	256.0	266.0	9	-	-	-	5
	266.0	268.0	9	-	f	-	5
	268.0	270.0	4	-	-	-	0.1
	270.0	271.0	4	-	f	-	0.1
	271.0	275.0	4	-	-	-	0.1
	275.0	276.0	4	-	f	-	0.1
	276.0	289.5	4	-	-	-	0.1
	285.0	286.0	4	-	f	-	0.1
	286.0	289.5	4	-	-	-	0.1
	289.5	297.0	4	-	f	-	0.1
BC2K25							
	0.0	40.0	0	-	-	-	0
	40.0	70.6	7	-	-	-	5

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	70.6	75.0	7	-	-	-	4
	75.0	76.7	7	-	-	qs	4
	76.7	77.7	7	-	f	-	4
	77.7	81.9	7	-	-	-	4
	81.9	84.7	7a	-	-	-	3
	84.7	85.7	7a	-	f	-	3
	85.7	88.0	7	-	-	-	2
	88.0	105.0	3a	-	-	qs	7
	105.0	112.3	3	-	-	qs	7
	112.3	112.4	10	-	-	qv	10
	112.4	115.0	3	-	-	-	2
	115.0	166.0	3a	-	-	qs	5
	166.0	191.0	3a	-	-	-	7
	191.0	198.3	2	-	f	-	1
	198.3	206.5	7a	-	-	-	10
	206.5	207.0	2	-	f	-	10
	207.0	210.0	2	-	f	-	25
	210.0	213.7	7a	-	-	-	5
	213.7	235.5	2	-	-	-	25
	235.5	240.0	9	-	-	-	15
	240.0	245.0	9	-	f	-	15
	245.0	249.7	2	-	f	-	5
	249.7	253.0	2	-	f	-	20
	253.0	258.7	2	-	-	-	20
	258.7	260.5	2	-	-	-	3
	260.5	261.3	10	-	-	qv	3
	261.3	300.0	1a	-	-	-	3
BC2K26							
	0.0	60.0	0	-	-	-	0
	60.0	61.0	10	-	-	qv	5
	61.0	61.8	10	-	f	qv	5
	61.8	65.0	10	-	-	qv	5
	65.0	65.2	10	-	f	qv	5
	65.2	68.3	10	-	-	qv	5
	68.3	68.6	10	-	f	qv	5
	68.6	70.0	10	-	-	qv	5
	70.0	70.2	10	-	f	qv	5
	70.2	71.5	10	-	-	qv	5
	71.5	71.8	10	-	f	qv	5
	71.8	76.0	10	-	-	qv	5
	76.0	78.0	10	-	f	qv	5
	78.0	81.0	10	-	-	qv	5
	81.0	81.1	10	-	f	qv	5
	81.1	81.5	10	-	-	qv	5
	81.5	81.6	10	0.061	-	qv	5
	81.6	82.1	10	0.061	f	qv	5
	82.1	82.5	10	0.061	-	qv	5
	82.5	83.0	10	0.061	-	qv	5
	83.0	83.1	10	0.061	-	qv	1
	83.1	84.5	10	0.061	f	qv	1
	84.5	85.0	10	0.061	-	qv	1
	85.0	87.4	10	-	-	qv	1
	87.4	98.2	2	-	-	-	1

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	98.2	99.1	2	-	-	qs	1
	99.1	100.0	2	-	-	-	1
	100.0	106.6	6	-	-	-	1
	106.6	107.8	10	-	-	qv	2
	107.8	108.7	6	-	-	-	1
	108.7	110.0	6	-	-	qs	1
	110.0	111.0	6	-	-	-	1
	111.0	111.5	6	0.072	-	-	1
	111.5	112.4	10	0.072	-	qv	1
	112.4	114.0	6	0.072	-	-	1
	114.0	115.0	6	0.072	-	-	10
	115.0	115.8	10	0.072	-	qv	1
	115.8	116.5	6	0.072	-	-	1
	116.5	118.0	10	0.072	-	qv	1
	118.0	125.8	6	0.072	-	-	1
	125.8	125.9	6	0.072	-	-	20
	125.9	126.7	2	0.072	f	-	15
	126.7	128.0	6	0.072	-	-	1
	128.0	134.0	6	-	-	-	1
	134.0	136.8	2	-	-	-	1
	136.8	136.9	2	-	f	-	1
	136.9	139.0	2	-	-	-	1
	139.0	139.2	2	-	f	-	1
	139.2	152.7	2	-	-	-	1
	152.7	156.0	7	-	-	-	15
	156.0	167.0	7	-	-	qs	5
	167.0	167.2	7	-	f	-	4
	167.2	187.8	7	-	-	-	4
	187.8	208.3	7	-	-	-	5
	208.3	209.3	7	-	-	-	25
	209.3	213.2	7	-	-	-	4
	213.2	224.5	7	-	-	-	50
	224.5	224.6	7	0.084	-	-	50
	224.6	225.7	7	0.084	f	-	50
	225.7	229.5	7	0.084	-	-	50
	229.5	230.0	3	-	-	-	10
	230.0	231.5	3	-	-	-	3
	231.5	235.3	3	-	-	-	4
	235.3	236.6	10	-	-	qv	4
	236.6	255.5	3	-	-	-	6
	255.5	256.0	3	0.054	-	-	4
	256.0	256.1	3	0.054	-	-	90
	256.1	256.2	3	0.054	-	-	3
	256.2	256.3	3	0.054	f	-	3
	256.3	257.0	3	0.054	-	-	1
	257.0	275.5	3	-	-	-	1
	275.5	284.7	1	-	-	-	3
	284.7	284.8	1	-	f	-	3
	284.8	287.0	1	-	-	-	3
	287.0	287.1	1	-	f	-	3
	287.1	291.0	1	-	-	-	3
	291.0	309.9	1	-	-	-	1
	309.9	313.7	2	-	-	-	3
	313.7	337.3	1	-	-	-	1
	337.3	337.5	1	-	f	-	1

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	337.5	340.0	1	-	-	-	1
	340.0	344.0	1	-	-	qs	1
	344.0	345.0	10	-	-	qv	1
	345.0	350.0	1	-	-	qs	1
BC2K27							
	0.0	42.0	0	-	-	-	0
	42.0	53.5	5b	-	-	-	0.5
	53.5	59.2	5	-	-	-	0.5
	59.2	61.0	5	-	f	-	0.5
	61.0	62.0	5	-	-	-	0.5
	62.0	70.0	2	-	-	-	0.5
	70.0	70.2	2	-	f	-	0.5
	70.2	71.2	2	-	-	-	0.5
	71.2	72.0	2	-	f	-	0.5
	72.0	81.5	10	-	f	qv	0.5
	81.5	81.6	10	-	f	qv	100
	81.6	88.5	10	-	f	qv	0.5
	88.5	90.3	2	-	f	-	3
	90.3	92.0	2	-	-	-	3
	92.0	93.5	2	-	-	-	10
	93.5	100.1	2	-	-	-	3
	100.1	100.6	10	-	-	qv	3
	100.6	102.6	2	-	-	-	3
	102.6	107.8	5	-	-	-	1
	107.8	118.0	6	-	-	-	1
	118.0	123.8	6	0.24	-	-	1
	123.8	124.0	6	0.24	f	-	15
	124.0	127.9	2	0.24	-	-	0.5
	127.9	128.1	2	0.24	f	-	0.5
	128.1	129.6	2	0.24	-	-	0.5
	129.6	129.7	2	0.24	f	-	0.5
	129.7	130.0	2	0.24	-	-	0.5
	130.0	135.5	2	-	-	-	0.5
	135.5	140.8	2	-	-	qs	0.5
	140.8	146.0	7	-	-	-	1
	146.0	149.3	7	0.179	-	-	1
	149.3	150.0	7	0.179	f	-	1
	150.0	151.3	7	-	-	-	1
	151.3	181.5	3	-	-	-	2
	181.5	188.4	7	-	-	-	1
	188.4	192.0	7	-	-	-	2
	192.0	195.3	7	-	-	-	5
	195.3	198.5	7	-	-	-	40
	198.5	206.6	7	-	-	qs	10
	206.6	220.0	3	-	-	qs	10
	220.0	230.0	9	-	-	-	5
	230.0	233.9	9	0.087	-	-	5
	233.9	234.2	9	0.087	-	-	80
	234.2	240.0	9	0.087	-	-	5
	240.0	261.5	9	0.087	-	-	15
	261.5	263.0	9	0.087	-	-	3
	263.0	264.5	9	0.087	f	-	3
	264.5	272.3	9	0.087	-	-	3
	272.3	273.4	9	0.087	f	-	3

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	273.4	275.0	9	0.087	-	-	3
	275.0	285.0	9	-	-	-	3
	285.0	287.5	9	-	f	-	3
	287.5	290.0	9	-	-	-	3
	290.0	292.0	9	0.433	-	-	50
	292.0	301.4	9	0.433	-	-	3
	301.4	301.8	9	0.433	f	-	3
	301.8	302.0	9	0.433	-	-	3
	302.0	305.7	9	0.433	-	-	25
	305.7	310.0	9	0.433	-	-	3
	310.0	321.1	9	-	-	-	3
	321.1	321.3	9	-	f	-	3
	321.3	327.3	9	-	-	-	3
	327.3	328.0	9	-	f	-	3
	328.0	335.7	9	-	-	-	3
	335.7	336.7	9	-	f	-	3
	336.7	340.0	9	-	-	-	3
	340.0	344.8	9	0.025	-	-	3
	344.8	345.0	9	0.025	-	-	20
	345.0	350.0	9	0.191	-	-	20
	350.0	352.0	9	-	-	-	2
	352.0	353.4	9	-	-	-	15
	353.4	395.0	9	-	-	-	3
	395.0	408.3	9	-	-	-	5
	408.3	408.8	9	-	-	-	15
	408.8	410.2	9	-	-	-	5
	410.2	411.5	9	-	-	-	10
	411.5	418.9	9	-	-	-	3
	418.9	420.5	9	-	-	-	10
	420.5	421.6	9	-	-	-	5
	421.6	421.7	10	-	-	qv	5
	421.7	423.5	9	-	-	-	5
	423.5	428.8	2	-	-	-	5
	428.8	430.0	2	-	f	-	5
BC2K28							
	0.0	34.0	0	-	-	-	0
	34.0	47.0	5	-	-	-	0.1
	47.0	53.5	5b	-	-	-	0.1
	53.5	54.2	5	-	-	-	0.1
	54.2	54.6	10	-	-	qv	0.1
	54.6	70.8	5	-	-	-	0.1
	70.8	70.9	5	-	f	-	0.1
	70.9	75.8	10	-	-	qv	0.5
	75.8	78.0	10	-	f	qv	4
	78.0	83.8	10	-	f	qv	0.5
	83.8	97.5	10	-	-	qv	0.5
	97.5	98.0	10	0.412	-	qv	0.5
	98.0	99.2	10	0.412	-	qv	50
	99.2	101.0	10	0.412	-	qv	0.5
	101.0	102.2	10	0.412	f	qv	0.5
	102.2	102.5	10	0.412	-	qv	2
	102.5	113.5	2	-	-	-	2
	113.5	125.0	6	-	-	qs	2
	125.0	131.3	6	0.112	-	qs	2

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	131.3	131.5	6	0.112	f	qs	2
	131.5	131.8	6	0.112	-	-	2
	131.8	136.2	2	-	-	-	1
	136.2	136.5	2	-	-	-	1
	136.5	138.0	2	-	-	-	1
	138.0	153.2	3	-	-	qs	1
	153.2	154.8	3	-	-	-	5
	154.8	169.9	3	-	-	-	4
	169.9	182.8	3	-	-	-	1
	182.8	183.4	3	-	f	-	1
	183.4	205.0	3	-	-	-	1
	205.0	225.3	3	-	-	qs	1
	225.3	240.0	7	-	-	-	5
	240.0	247.2	9	-	-	-	5
	247.2	248.5	9	-	f	-	5
	248.5	260.0	9	-	-	-	5
	260.0	267.0	9	0.105	-	-	5
	267.0	274.5	9	0.105	-	-	15
	274.5	275.0	9	0.105	-	-	10
	275.0	305.0	9	-	-	-	10
	305.0	310.0	9	-	-	-	5
	310.0	311.2	9	0.032	-	-	5
	311.2	318.0	9	0.032	-	-	30
	318.0	320.0	9	0.032	-	-	1
	320.0	364.3	9	-	-	-	1
	364.3	373.0	9	-			3
	373.0	385.0	9	-			1
	385.0	387.5	9	-			7
	387.5	409.5	9	-			1
	409.5	410.6	9	-			40
	410.6	480.0	9	-			2
	480.0	490.0	9	-			1
BC2K29							
	0.0	34.0	0	-	-	-	0
	34.0	44.0	5	-	-	-	0.1
	44.0	51.5	5b	-	-	-	0.1
	51.5	67.5	5	-	-	-	0.1
	67.5	67.6	10	-	-	qv	0.1
	67.6	70.4	5	-	-	-	0.1
	70.4	78.6	2	-	-	-	1
	78.6	78.9	10	0.038	-	qv	3
	78.9	79.2	10	0.038	f	qv	3
	79.2	85.0	10	0.038	-	qv	3
	85.0	95.1	10	-	-	qv	3
	95.1	95.3	10	-	-	qv	3
	95.3	104.5	10	-	-	qv	3
	104.5	105.3	10	-	f	qv	3
	105.3	108.3	2	-	-	-	0.1
	108.3	108.4	10	-	-	qv	0.1
	108.4	108.8	2	-	-	-	0.1
	108.8	121.6	6	-	-	-	0.5
	121.6	121.7	10	-	-	qv	0.5
	121.7	154.5	6	-	-	-	0.5
	154.5	160.3	6	-	-	qs	0.5

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	160.3	174.3	6	-	-	-	0.5
	174.3	174.8	6	-	-	-	5
	174.8	180.7	6	-	-	-	15
	180.7	183.4	6	0.585	-	-	50
	183.4	185.4	6	-	-	-	2
	185.4	191.3	2	-	-	-	0.5
	191.3	191.4	2	-	f	-	0.5
	191.4	192.2	2	-	-	-	0.5
	192.2	193.1	2	-	f	-	0.5
	193.1	195.8	2	-	-	-	0.5
	195.8	198.9	4	0.608	-	-	25
	198.9	200.0	6	0.608	-	-	1
	200.0	205.7	6	-	-	-	1
	205.7	213.1	6	-	-	-	5
	213.1	213.5	6	0.421	f	-	5
	213.5	214.1	6	0.421	-	-	5
	214.1	215.5	2	0.421	-	-	35
	215.5	216.5	8	0.421	-	-	20
	216.5	220.0	8	-	-	-	20
	220.0	228.5	8	0.804	-	-	20
	228.5	231.2	8	0.804	-	-	35
	231.2	231.6	8	0.804	-	-	50
	231.6	239.0	8	0.804	-	-	35
	239.0	242.9	8	0.804	-	-	40
	242.9	247.5	8	0.804	-	-	35
	247.5	248.0	8	0.804	f	-	35
	248.0	252.1	8	0.804	-	-	35
	252.1	252.4	7	-	f	-	3
	252.4	253.7	7	-	-	-	3
	253.7	255.0	7	-	-	qs	5
	255.0	256.8	7	-	-	-	10
	256.8	261.2	9	-	-	-	0.5
	261.2	261.4	9	-	f	-	0.5
	261.4	262.6	9	-	-	-	0.5
	262.6	263.0	9	-	-	qs	0.5
	263.0	277.7	9	-	-	-	0.5
	277.7	301.8	9	-	-	-	10
	301.8	315.7	9	-	-	-	1
	315.7	316.6	9	-	-	-	10
	316.6	323.5	9	-	-	-	1
	323.5	325.2	9	-	-	-	50
	325.2	344.0	9	-	-	-	5
	344.0	353.0	9	-	-	-	1
	353.0	370.6	9	-	-	-	5
	370.6	372.6	9	-	-	-	1
	372.6	385.0	9	-	-	2	1
	385.0	385.1	9	-	f	2	1
	385.1	386.2	9	-	-	2	1
	386.2	386.3	9	-	f	2	1
	386.3	386.5	9	-	-	2	1
	386.5	386.6	9	-	f	2	1
	386.6	387.0	9	-	-	2	1
	387.0	414.2	9	-	-	-	1
	414.2	418.4	9	-	-	-	20
	418.4	421.4	9	-	-	-	1

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	421.4	430.0	9	-	-	-	12
	430.0	442.7	9	-	-	-	5
	442.7	443.0	2	-	-	-	5
	443.0	443.2	2	-	f	-	1
	443.2	443.6	2	-	-	-	1
	443.6	443.7	2	-	f	-	1
	443.7	447.0	2	-	-	-	1
	447.0	449.7	2	-	-	-	4
	449.7	457.6	2	-	-	-	1
	457.6	473.6	1	-	-	-	2
	473.6	473.7	1	-	f	-	2
	473.7	475.0	1	-	-	-	2
	475.0	480.9	3	-	-	-	1
	480.9	481.0	3	-	f	-	1
	481.1	500.0	3	-	-	-	1
BC2K30							
	0.0	44.0	0	-	-	-	0
	44.0	70.0	5a	-	-	-	0.1
	70.0	79.0	5a/b	-	-	-	0.1
	79.0	99.0	5a/b	-	-	-	0.1
	99.0	116.3	5a	-	-	-	0.1
	116.3	127.5	2	-	-	qs	0.1
	127.5	133.5	5	-	-	-	1
	133.5	133.9	2	-	f	-	0.1
	133.9	139.5	10	-	-	qv	0.1
	139.5	140.5	2	-	f	-	0.1
	140.5	145.0	2	-	-	-	1
	145.0	156.0	6	-	-	-	1
	156.0	160.0	2	-	f	-	1
	160.0	165.0	6	0.266	-	-	25
	165.0	169.5	6	0.266	-	-	5
	169.5	173.0	6	0.266	-	-	25
	173.0	179.0	6	0.266	-	-	5
	179.0	186.0	6	0.266	-	qs	25
	186.0	192.0	6	0.266	-	-	5
	192.0	197.5	6	0.266	-	-	25
	197.5	200.5	6	0.266	-	-	5
	200.5	202.0	6	0.266	-	-	25
	202.0	205.0	6	-	-	-	5
	205.0	211.0	7	-	-	-	5
	211.0	212.5	7	-	-	-	5
	212.5	224.0	7	-	-	-	5
	224.0	230.0	9	-	-	-	10
	230.0	234.5	9	0.031	-	-	10
	234.5	245.0	9	-	-	-	5
	245.0	255.0	9	-	-	-	10
	255.0	269.0	9	0.046	-	-	10
	269.0	280.0	9	0.046	-	-	5
	280.0	285.0	9	-	-	-	5
	285.0	295.0	9	-	-	-	5
	295.0	307.5	9	0.154	-	-	5
	307.5	326.5	9	0.154	-	-	40
	326.5	334.5	9	0.154	-	-	5
	334.5	342.0	9	0.154	-	-	40

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	342.0	346.2	9	0.154	-	-	5
	346.2	347.2	9	0.154	-	-	40
	347.2	357.5	9	0.154	-	-	5
	357.5	362.0	9	0.154	-	-	40
	362.0	370.0	9	0.154	-	-	5
	370.0	378.0	9	0.154	f	-	5
	378.0	390.0	9	0.154	-	-	5
	390.0	395.0	4	0.154	f	-	5
	295.0	362.0	4	0.154	f	-	5
	362.0	390.0	4	-	f	-	5
	390.0	399.0	4	-	f	-	5
	399.0	420.0	1	-	-	-	3
	420.0	450.0	1	-	-	-	1
BC2K31							
	0.0	30.0	0	-	-	-	0
	30.0	40.0	5	-	-	-	0.5
	40.0	50.0	5	-	f	-	0.5
	50.0	52.0	5	-	-	-	0.5
	52.0	57.5	5	-	-	-	3
	57.5	67.5	5	-	-	-	0.5
	67.5	72.2	5b	-	-	-	0.5
	72.2	79.5	5a/b	-	-	-	0.5
	79.5	90.0	5b	-	-	-	0.5
	90.0	105.0	5a/b	-	-	-	0.5
	105.0	127.9	5	-	-	-	0.5
	127.9	129.2	2	-	-	-	1
	129.2	129.5	2	-	f	-	1
	129.5	132.0	2	-	-	-	1
	132.0	132.8	10	-	-	qv	1
	132.8	133.2	5	-	f	-	0.5
	133.2	180.7	5	-	-	-	0.5
	180.7	190.8	2	-	-	-	2
	190.8	195.0	2	0.068	-	-	4
	195.0	199.3	2	0.068	-	-	3
	199.3	210.4	6	0.288	-	-	3
	210.4	214.8	7	0.288	-	-	50
	214.8	216.0	7	0.288	-	-	10
	216.0	228.0	7	0.288	-	-	60
	228.0	232.6	7	0.288	-	-	10
	232.6	235.5	7	0.288	-	-	20
	235.5	250.0	4	0.288	f	-	5
	250.0	255.2	7a	0.288	-	-	15
	255.2	262.5	7a	0.288	-	-	1
	262.5	270.0	7a	0.288	-	-	15
	270.0	272.9	7a	0.288	-	-	5
	272.9	273.2	7a	0.288	-	-	40
	273.2	280.0	7a	0.288	-	-	0.5
	280.0	286.5	2	-	-	-	0.5
	286.5	293.1	6	-	-	-	0.5
	293.1	302.0	2	-	-	-	2
	302.0	330.0	7a	-	-	-	0.5
	330.0	345.0	7	0.067	-	-	12
	345.0	355.8	9	-	-	-	0.5
	355.8	365.5	7a	-	-	-	0.5

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	365.5	400.6	9	-	-	-	0.5
	400.6	402.0	9	-	f	-	0.5
	402.0	410.0	9	-	-	-	0.5
	410.0	414.2	9	-	f	-	0.5
	414.2	421.6	9	-	-	-	0.5
	421.6	422.2	9	-	-	-	15
	422.2	439.0	9	-	-	-	1
	439.0	446.0	9	-	-	-	20
	446.0	450.8	9	-	-	-	1
	450.8	454.3	9	-	-	-	1
	454.3	471.2	9	-	-	-	1
	471.2	483.2	9	-	-	-	1
	483.2	510.0	9	-	-	-	3
	510.0	516.0	9	-	-	-	0.5
	516.0	520.0	3	-	f	qs	0.5
BC2K32							
	0.0	49.0	0	-	-	-	0
	49.0	56.0	5b	-	-	-	0.1
	56.0	65.4	5	-	-	-	0.1
	65.4	69.8	5	-	-	qs	0.1
	69.8	70.0	5	-	-	-	0.1
	70.0	70.1	10	-	-	qv	0.1
	70.1	70.7	5	-	-	-	0.1
	70.7	73.4	2	-	-	-	2
	73.4	73.5	5	-	f	-	0.5
	73.5	77.0	5	-	-	-	0.5
	77.0	77.1	5	-	f	-	1
	77.1	86.5	5	-	-	-	1
	86.5	87.5	5	-	f	-	1
	87.5	88.0	10	-	-	qv	0.5
	88.0	89.0	10	-	f	qv	5
	89.0	94.7	10	-	f	qv	1
	94.7	101.8	10	-	f	qv	2
	101.8	107.0	2	-	-	qs	2
	107.0	112.3	6	-	-	qs	2
	112.3	117.0	2	-	f	-	2
	117.0	117.1	2	-	-	-	7
	117.1	133.3	6	0.094	-	-	7
	133.3	138.0	6	0.094	-	-	4
	138.0	140.0	6	0.094	-	qs	4
	140.0	142.3	6	-	-	qs	4
	142.3	142.5	6	-	f	-	4
	142.5	144.5	6	-	-	-	4
	144.5	145.0	6	-	-	qs	4
	145.0	145.6	2	0.036	-	qs	4
	145.6	145.8	10	0.036	-	qv	4
	145.8	149.0	2	0.036	-	-	4
	149.0	154.8	3	-	-	-	4
	154.8	162.7	7	-	-	-	2
	162.7	165.3	7	-	-	qs	2
	165.3	178.9	2	-	-	qs	1
	178.9	179.6	2	-	f	qs	1
	179.6	180.0	2	-	-	qs	1
	180.0	183.3	3	-	-	qs	4

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	183.3	190.0	3	-	-	-	4
	190.0	197.0	6	-	-	-	0.5
	197.0	203.6	8	0.386	-	-	40
	203.6	203.8	8	0.386	-	-	70
	203.8	204.1	8	0.386	-	-	40
	204.1	204.6	8	0.386	-	-	80
	204.6	205.6	8	0.386	-	-	40
	205.6	206.1	8	0.386	-	-	80
	206.1	208.5	8	0.386	-	-	40
	208.5	221.0	8	0.386	-	-	10
	221.0	229.8	8	0.386	-	-	10
	229.8	234.7	8	0.386	-	qs	10
	234.7	238.0	8	0.386	-	-	10
	238.0	239.5	8	0.386	-	-	25
	239.5	244.0	8	0.386	-	-	25
	244.0	244.7	8	0.386	f	-	25
	244.7	247.9	8	0.386	-	-	25
	247.9	248.0	8	0.386	f	-	25
	248.0	250.0	8	0.386	-	-	10
	250.0	250.7	9	0.386	-	-	5
	250.7	250.8	9	0.386	f	-	5
	250.8	257.8	9	0.386	-	-	5
	257.8	260.4	9	0.386	-	-	15
	260.4	262.1	9	0.386	-	-	5
	262.1	262.2	9	0.386	f	-	5
	262.2	263.5	9	0.386	-	-	5
	263.5	265.0	9	0.386	f	-	5
	265.0	276.0	9	0.386	-	-	5
	276.0	277.3	10	0.386	-	qv	5
	277.3	280.0	9	0.386	-	-	5
	280.0	295.0	9	0.386	-	-	2
	295.0	305.0	9	-	-	-	2
	305.0	309.3	9	0.263	-	-	2
	309.3	311.5	9	0.263	-	-	20
	311.5	316.0	9	0.263	-	-	2
	316.0	316.1	9	0.263	f	-	2
	316.1	320.0	9	0.263	-	-	2
	320.0	323.1	9	0.263	-	-	10
	323.1	324.5	9	0.263	-	-	2
	324.5	324.6	9	0.263	f	-	2
	324.6	326.0	9	0.263	-	-	2
	326.0	329.0	9	0.263	-	-	10
	329.0	329.1	9	0.263	f	-	10
	329.1	331.0	9	0.263	-	-	10
	331.0	333.6	9	0.263	-	-	2
	333.6	333.7	9	0.263	f	-	2
	333.7	338.0	9	0.263	-	-	2
	338.0	342.3	9	0.263	-	-	10
	342.3	345.0	9	0.263	-	-	2
	345.0	365.7	9	-	-	-	2
	365.7	365.8	9	-	f	-	2
	365.8	367.6	9	-	-	-	2
	367.6	367.9	9	-	f	-	2
	367.9	368.3	9	-	-	-	2
	368.3	368.4	9	-	f	-	2

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	368.4	408.6	9	-	-	-	2
	408.6	409.0	9	-	-	-	10
	409.0	411.0	9	-	-	-	2
	411.0	411.4	9	-	-	-	10
	411.4	413.0	9	-	-	-	2
	413.0	413.8	9	-	-	-	10
	413.8	421.8	9	-	-	-	2
	421.8	430.2	1	-	-	-	2
	430.2	430.5	1	-	f	-	2
	430.5	437.3	1	-	-	-	2
	437.3	437.5	1	-	f	-	2
	437.5	440.0	1	-	-	-	2
BC2K33							
	0.0	64.0	0	-	-	-	0
	64.0	70.8	3	-	-	-	0.1
	70.8	71.5	10	-	-	qv	10
	71.5	71.6	10	-	f	qv	10
	71.6	72.8	10	-	-	qv	10
	72.8	99.8	3	-	-	-	0.1
	99.8	99.9	3	-	f	-	0.1
	99.9	101.6	3	-	-	-	0.1
	101.6	102.0	3	-	f	-	0.1
	102.0	125.0	1	-	-	-	0.1
	125.0	125.2	1	-	f	-	0.1
	125.2	166.8	1	-	-	-	0.1
	166.8	173.8	1	-	-	-	1
	173.8	173.9	10	-	-	qv	0.1
	173.9	187.4	1	-	-	-	0.1
	187.4	204.6	1	-	-	qs	0.1
	204.6	204.7	2	-	f	-	5
	204.7	215.0	2	-	-	-	5
	215.0	216.0	2	-	-	-	7
	216.0	216.4	2	-	-	-	1
	216.4	217.3	2	-	f	-	1
	217.3	219.4	2	-	-	-	1
	219.4	223.7	6	-	-	-	2
	223.7	223.8	2	0.224	-	-	2
	223.8	225.3	2	0.224	-	-	5
	225.3	225.4	2	0.224	2	-	5
	225.4	226.5	7	0.224	2	-	5
	226.5	232.3	7	0.224	-	-	5
	232.3	233.0	7	0.224	-	-	15
	233.0	236.0	7	0.224	-	-	5
	236.0	237.4	7	0.224	-	-	40
	237.4	238.0	7	0.224	-	-	5
	238.0	240.6	9	0.224	-	-	5
	240.6	244.0	9	0.224	-	-	10
	244.0	245.0	9	0.224	-	-	5
	245.0	257.6	9	-	-	-	5
	257.6	257.8	9	-	-	-	10
	257.8	257.9	9	-	f	-	10
	257.9	261.0	9	-	-	-	10
	261.0	288.9	9	-	-	-	1.5
	288.9	290.0	9	-	-	-	0.1

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	290.0	312.0	9	-	-	qs	0.1
	312.0	327.0	9	-	-	-	0.5
	327.0	329.0	9	-	f	-	0.5
	329.0	362.5	9	-	-	-	0.5
	362.5	369.0	9	-	-	-	2
	369.0	370.0	9	-	-	-	1
	370.0	376.0	6	-	-	-	1
	376.0	376.3	6	-	-	-	3
	376.3	391.6	6	-	-	-	0.5
	391.6	423.4	6	-	-	-	1
	423.4	424.5	6	-	f	-	0.5
	424.5	485.3	6	-	-	-	0.5
	485.3	505.5	2	-	-	-	1
	505.5	506.4	2	-	f	-	1
	506.4	506.5	6	-	f	-	0.5
	506.5	516.8	6	-	-	-	0.5
	516.8	516.9	10	-	-	qv	0.5
	516.9	521.0	6	-	-	-	0.5
	521.0	528.5	2	-	-	-	0.5
	528.5	529.0	2	-	f	-	0.5
	529.0	530.0	2	-	-	-	0.5
	530.0	533.8	2	-	-	-	3
	533.8	536.0	7	-	-	-	2
	536.0	538.0	7	-	-	qs	2
	538.0	551.0	7	-	-	-	2
	551.0	554.0	7	-	-	qs	2
	554.0	558.0	7	-	-	-	2
	558.0	560.0	10	-	-	qv	5
	560.0	563.2	7	-	-	-	1
	563.2	565.8	6	-	-	-	1
	565.8	579.4	7	-	-	-	1
	579.4	581.6	2	-	-	-	1
	581.6	581.9	2	-	f	-	1
	581.9	582.8	2	-	-	-	1
	582.8	583.5	10	0.337	-	qv	1
	583.5	585.7	10	0.337	-	qv	10
	585.7	594.0	10	0.337	f	qv	15
	594.0	596.0	10	0.337	f	qv	50
	596.0	599.3	10	0.337	f	qv	1
	599.3	599.5	5	-	f	qv	1
	599.5	606.3	5	-	-	-	1
	606.3	606.7	5	-	f	-	1
	606.7	607.0	5	-	-	-	1
	607.0	609.3	5	-	-	qv	1
	609.3	610.2	5	-	-	-	1
	610.2	611.6	10	-	f	qv	1
	611.6	627.5	5	-	-	-	1
	627.5	629.0	5	-	f	-	1
	629.0	635.0	5	-	-	-	1
	635.0	635.3	5	-	-	qs	1
	635.3	641.8	5	-	-	-	1
	641.8	645.0	5	-	-	qs	1
	645.0	669.0	5	-	-	-	1
	669.0	669.6	5	-	-	-	2
	669.6	670.0	10	-	-	qv	2

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	670.0	673.0	5	-	-	-	2
	673.0	674.0	10	-	-	qv	2
	674.0	677.5	5	-	-	-	2
	677.5	678.5	10	-	-	qv	2
	678.5	680.1	5	-	-	-	2
	680.1	680.2	10	-	-	qv	2
	680.2	687.5	5	-	-	-	2
	687.5	688.5	10	-	-	qv	2
	688.5	695.0	5	-	-	qs	2
	695.0	696.0	10	-	-	qv	2
	696.0	702.0	5	-	-	-	2
	702.0	704.0	10	-	-	qv	2
	704.0	704.8	5	-	-	-	2
	704.8	705.3	10	-	-	qv	2
	705.3	710.0	5	-	-	-	2
BC2K-34							
	0.0	66.0	0	-	-	-	0
	66.0	75.6	7	-	-	-	3
	75.6	77.0	7	-	f	-	6
	77.0	80.0	7	-	-	-	3
	80.0	98.0	3	-	-	-	1
	98.0	99.4	6	-	-	-	4
	99.4	99.5	6	-	f	-	4
	99.5	110.7	6	-	-	-	4
	110.7	111.4	6	-	-	qs	4
	111.4	112.9	6	-	-	-	4
	112.9	130.0	3	-	-	-	0.5
	130.0	130.3	3	-	f	-	0.5
	130.3	140.7	7	-	-	-	5
	140.7	169.0	6	-	-	-	2
	169.0	169.1	10	-	-	qv	2
	169.1	192.8	6	-	-	-	2
	192.8	195.2	2	-	-	-	1
	195.2	196.7	2	-	-	qv	1
	196.7	199.2	2	-	-	-	1
	199.2	199.4	10	-	f	qv	1
	199.4	199.8	2	-	-	-	1
	199.8	200.0	2	-	-	-	1
	200.0	200.2	2	-	-	qv	1
	200.2	204.5	2	-	-	-	1
	204.5	210.0	2	-	-	qs	1
	210.0	213.0	2	-	-	-	1
	213.0	215.0	10	-	-	qv	1
	215.0	220.0	2	-	f	-	1
	220.0	221.0	5	-	f	-	0.5
	221.0	226.1	5	-	-	-	0.5
	226.1	228.1	5	-	f	-	0.5
	228.1	230.0	5	-	-	-	0.5
	230.0	250.0	2	-	-	-	2
	250.0	251.0	10	-	-	qv	2
	251.0	271.3	2	-	-	-	2
	271.3	284.0	5	-	-	-	1
	284.0	288.0	5a	-	-	-	0.5
	288.0	295.0	5b	-	-	-	0.5

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	295.0	350.0	5a	-	-	-	0.5
BC2K-35							
	0.0	60.0	0	-	-	-	0
	60.0	71.3	2	-	-	-	2
	71.3	89.5	6	-	-	qs	3
	89.5	119.9	6	-	-	-	3
	119.9	120.0	6	-	f	-	3
	120.0	133.0	6	-	-	-	3
	133.0	138.0	3	-	-	-	2
	138.0	145.5	3a	-	-	-	2
	145.5	162.3	3	-	-	-	2
	162.3	162.4	9	-	f	-	5
	162.4	168.0	9	-	-	-	5
	168.0	187.0	9	-	-	-	2
	187.0	187.1	9	-	f	-	2
	187.1	189.3	9	-	-	-	2
	189.3	189.4	9	-	f	-	2
	189.4	189.9	9	-	-	-	2
	189.9	190.0	9	-	f	-	2
	190.0	192.0	9	-	-	-	2
	192.0	196.0	9	-	-	-	10
	196.0	199.6	9	-	-	-	3
	199.6	199.7	9	-	f	-	3
	199.7	208.5	9	-	-	-	3
	208.5	208.8	9	-	f	-	3
	212.0	212.0	9	-	-	-	3
	212.0	215.3	9	-	-	-	1
	215.3	216.0	9	-	f	-	1
	216.0	220.0	9	-	-	-	1
	220.0	229.1	9	-	-	-	3
	229.1	229.4	9	-	f	-	3
	229.4	237.5	9	-	-	-	3
	237.5	237.6	9	-	-	-	15
	237.6	240.2	9	-	-	-	2
	240.2	241.0	3	-	-	-	2
	241.0	248.5	3	-	-	-	5
	248.5	257.8	3	-	-	-	2
	257.8	258.0	3	-	-	qs	2
	258.0	259.2	3	-	-	-	10
	259.2	274.5	3	-	-	-	2
	274.5	274.6	3	-	f	-	2
	274.6	281.2	3	-	-	-	2
	281.2	290.2	3	-	f	-	1
	290.2	295.6	3	-	f	-	3
	295.6	296.6	10	-	f	qv	5
	296.6	300.6	3	-	f	-	5
	300.6	301.5	3	-	-	-	3
	301.5	303.3	2	-	-	-	10
	303.3	303.7	2	-	f	-	10
	303.7	304.4	2	-	-	-	10
	304.4	305.6	2	-	f	-	10
	305.6	306.6	2	-	-	-	10
	306.6	331.7	1	-	-	-	3
	331.7	332.2	10	-	f	qv	3

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	332.2	339.5	1	-	-	-	3
	339.5	340.0	1	-	f	-	3
	340.0	343.1	1	-	-	-	3
	343.1	343.3	1	-	f	-	3
	343.3	350.0	1	-	-	-	3
BC2K-36							
	0.0	70.0	0	-	-	-	0
	70.0	82.9	2	-	-	-	0.5
	82.9	83.5	10	-	-	qv	2
	83.5	83.7	6	-	f	qs	1
	83.7	86.0	6	-	-	qs	1
	86.0	86.2	6	-	f	qs	1
	86.2	107.0	6	-	-	qs	1
	107.0	111.4	6	-	-	-	1
	111.4	111.6	6	-	f	-	1
	111.6	118.5	6	-	-	-	1
	118.5	120.3	10	-	-	qv	5
	120.3	137.8	6	-	-	-	1
	137.8	138.0	6	-	-	-	5
	138.0	149.8	6	-	-	-	3
	149.8	150.1	6	-	f	-	3
	150.1	152.2	6	-	-	-	3
	152.2	154.2	6	-	f	-	3
	154.2	156.3	6	-	-	-	3
	156.3	157.4	3a	-	-	-	1
	157.4	157.7	3a	-	f	-	1
	157.7	159.8	3a	-	-	-	1
	159.8	159.9	3a	-	f	-	1
	159.9	162.0	3a	-	-	-	1
	162.0	163.7	3a	-	-	-	3
	163.7	164.6	3a	-	-	-	7
	164.6	170.0	3a	-	-	-	1
	170.0	185.0	3a	-	-	-	2
	185.0	192.2	3a	-	-	-	1
	192.2	195.5	6	-	-	-	5
	195.5	196.5	3a	-	-	-	2
	196.5	208.2	9	-	-	-	8
	208.2	211.0	9	-	-	-	4
	211.0	211.7	9	-	-	-	10
	211.7	232.0	9	-	-	-	2
	232.0	250.0	9	-	-	-	3
	250.0	282.0	9	-	-	-	2
	282.0	292.0	9	-	f	-	4
	292.0	292.6	9	-	f	-	1
	292.6	294.5	9	-	-	-	1
	294.5	295.0	9	-	f	-	1
	295.0	298.8	9	-	-	-	1
	298.8	299.2	9	-	f	-	1
	299.2	304.8	9	-	-	-	1
	304.8	308.0	9	-	-	-	4
	308.0	312.7	9	-	-	-	1
	312.7	314.2	9	-	f	-	3
	314.2	312.7	9	-	-	-	2
	312.7	314.2	9	-	f	-	2

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	314.2	315.5	9	-	-	-	2
	315.5	316.3	9	-	f	-	2
	316.3	319.4	9	-	-	-	2
	319.4	319.5	9	-	f	-	2
	319.5	333.0	3	-	-	qs	2
	333.0	333.4	10	-	-	qs	30
	333.4	337.0	3	-	-	qs	2
	337.0	341.5	3	-	-	qs	5
	341.5	341.6	3	-	f	qs	5
	341.6	346.0	3	-	-	qs	5
	346.0	358.0	3	-	-	qs	2
	358.0	366.0	3	-	-	qs	5
	366.0	366.1	3	-	f	qs	5
	366.1	392.2	3	-	-	qs	5
	392.2	392.4	3	-	f	qs	5
	392.4	394.0	3	-	-	qs	5
	394.0	406.7	3	-	-	qs	10
	406.7	409.0	1	-	-	-	2
	409.0	409.1	1	-	f	-	2
	409.1	430.4	1	-	-	-	2
	430.4	430.8	1	-	f	-	2
	430.8	432.1	1	-	-	-	2
	432.1	439.3	1	-	f	-	2
	439.3	441.5	1	-	-	-	2
	441.5	441.9	1	-	f	-	2
	441.9	443.3	1	-	-	-	2
	443.3	445.0	1	-	-	-	1
	445.0	445.1	1	-	f	-	1
	445.1	446.0	1	-	-	-	1
	446.0	446.1	1	-	f	-	1
	446.1	449.0	1	-	-	-	1
	449.0	450.0	1	-	f	-	1
BC2K-37							
	0.0	40.0	0	-	-	-	0
	40.0	53.0	5	-	-	-	0.1
	53.0	56.0	5b	-	-	-	0.1
	56.0	56.7	5b	-	f	-	0.1
	56.7	59.0	5b	-	-	-	0.1
	59.0	60.0	5b	-	f	-	0.1
	60.0	61.0	5b	-	-	-	0.1
	61.0	61.3	5b	-	f	-	0.1
	61.3	62.0	5b	-	-	-	0.1
	62.0	62.1	5b	-	f	-	0.1
	62.1	62.3	5b	-	-	-	0.1
	62.3	62.4	5b	-	f	-	0.1
	62.4	63.3	5b	-	-	-	0.1
	63.3	63.4	5b	-	f	-	0.1
	63.4	69.7	5b	-	-	-	0.1
	69.7	69.8	5b	-	f	-	0.1
	69.8	71.0	5b	-	-	-	0.1
	71.0	71.1	5b	-	f	-	2
	71.1	71.8	5b	-	-	-	2
	71.8	71.9	5b	-	f	-	0.5
	71.9	79.6	5b	-	-	-	0.5

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	79.6	80.0	5b	-	f	-	0.5
	80.0	85.0	5b	-	-	-	0.5
	85.0	90.0	5	-	-	-	1
	90.0	90.4	5	-	f	-	1
	90.4	101.3	5	-	-	-	1
	101.3	101.6	5	-	f	-	1
	101.6	108.0	2	-	f	-	2
	108.0	110.2	6	-	-	qs	2
	110.2	110.4	6	-	f	qs	2
	110.4	112.0	6	-	-	qs	2
	112.0	115.0	10	-	-	qv	2
	115.0	117.6	6	-	-	qs	2
	117.6	118.5	10	-	f	qv	1
	118.5	119.0	6	-	-	qs	0.5
	119.0	120.0	10	-	-	qv	0.5
	120.0	127.2	6	-	-	-	0.5
	127.2	127.9	10	-	-	qv	0.5
	127.9	129.0	6	-	-	-	0.5
	129.0	137.1	6	-	-	-	2
	137.1	137.4	6	-	f	-	2
	137.4	145.7	6	-	-	-	2
	145.7	146.0	10	-	-	qv	2
	146.0	147.5	6	-	-	-	2
	147.5	148.3	10	-	-	qv	8
	148.3	169.2	6	-	-	-	0.5
	169.2	169.5	10	-	-	qv	0.5
	169.5	171.6	6	-	-	-	0.5
	171.6	171.9	10	-	-	qv	0.5
	171.9	176.0	6	-	-	-	0.5
	176.0	179.0	6	-	-	qs	0.5
	179.0	189.5	6	-	-	-	1
	189.5	190.0	10	-	f	qv	1
	190.0	195.2	6	-	-	-	1
	195.2	195.5	6	-	-	-	3
	195.5	198.0	6	-	f	-	3
	198.0	201.1	2	-	f	-	1
	201.1	201.6	2	-	-	-	1
	201.6	223.4	2	-	-	qs	1
	223.4	255.0	3	-	-	-	0.5
	255.0	263.4	3a	-	-	-	0.5
	263.4	263.5	3a	-	f	-	0.5
	263.5	265.6	3a	-	-	-	0.5
	265.6	265.7	10	-	-	qv	0.5
	265.7	268.4	3a	-	-	-	0.5
	268.4	268.5	3a	-	f	-	0.5
	268.5	274.7	3a	-	-	-	0.5
	274.7	275.4	3a	-	f	qs	0.5
	275.4	285.8	3a	-	-	qs	0.5
	285.8	287.6	3a	-	f	qs	0.5
	287.6	295.7	9	-	-	-	0.5
	295.7	312.2	9	-	f	-	0.5
	312.2	313.5	9	-	f	-	2
	313.5	314.5	9	-	-	-	2
	314.5	315.0	9	-	-	-	50
	315.0	320.0	9	-	-	-	2

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	320.0	326.2	9	-	-	-	8
	326.2	330.9	9	-	-	-	3
	330.9	331.1	9	-	-	-	50
	331.1	339.0	9	-	-	-	2
	339.0	340.3	9	-	-	-	40
	340.3	342.0	9	-	-	-	8
	342.0	348.5	9	0.031	-	-	8
	348.5	350.5	4	0.031	-	-	15
	350.5	350.6	4	0.031	f	-	15
	350.6	350.8	4	0.031	-	-	15
	350.8	352.9	7a	-	-	-	2
	352.9	354.1	6a	-	-	-	5
	354.1	354.3	7a	-	f	-	2
	354.3	355.7	7a	-	-	-	2
	355.7	355.8	7a	-	f	-	2
	355.8	356.2	7a	-	-	-	2
	356.2	356.3	7a	-	f	-	2
	356.3	358.5	7a	-	-	-	2
	358.5	360.0	2	-	f	-	6
	360.0	380.8	3	-	-	-	3
	380.8	384.2	3	-	-	qs	3
	384.2	402.0	3	-	-	-	3
	402.0	407.3	3	-	-	qs	3
	407.3	409.5	3	-	-	-	3
	409.5	410.0	3	-	f	-	3
BC2K-38							
	0.0	56.0	0	-	-	-	0
	56.0	60.0	5	-	-	-	5
	60.0	78.0	5	-	-	-	0.1
	78.0	79.0	2	-	-	-	2
	79.0	87.5	5	-	-	-	0.1
	87.5	87.8	5	-	f	-	0.1
	87.8	89.0	5	-	-	-	0.1
	89.0	89.1	5	-	f	-	0.1
	89.1	90.0	5	-	-	-	0.1
	90.0	99.6	2	-	-	-	1
	99.6	100.0	2	-	f	-	1
	100.0	101.4	6	-	-	-	1
	101.4	104.0	10	-	-	qv	5
	104.0	106.0	6	-	-	-	2
	106.0	108.0	6	-	-	qs	10
	108.0	110.0	10	-	f	qv	15
	110.0	110.8	10	0.033	f	qv	15
	110.8	114.8	6	0.033	-	-	4
	114.8	115.0	10	0.033	-	qv	4
	115.0	115.8	10	-	-	qv	4
	115.8	119.0	6	-	-	-	4
	119.0	119.4	6	-	f	-	4
	119.4	120.0	6	-	-	-	4
	120.0	121.1	6	-	f	-	4
	121.1	130.0	6	-	-	-	4
	130.0	152.0	6	-	-	-	1
	152.0	152.6	6	-	f	-	1
	152.6	158.4	6	-	-	-	1

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	158.4	158.7	2	-	-	-	2
	158.7	159.0	2	-	f	-	2
	159.0	164.5	2	-	-	-	2
	164.5	171.0	3a	-	-	-	0.5
	171.0	173.0	9	-	-	-	5
	173.0	178.5	6	-	-	-	1
	178.5	187.0	2	-	-	-	2
	187.0	190.0	6	-	-	-	0.1
	190.0	196.0	9	-	-	-	2
	196.0	206.0	9	-	-	-	10
	206.0	222.6	9	-	-	-	3
	222.6	229.0	9	-	-	-	10
	229.0	247.0	9	-	-	-	5
	247.0	265.0	9	-	f	-	15
	265.0	275.0	9	0.050	f	-	15
	275.0	285.0	9	-	-	-	5
	285.0	289.5	7	0.092	-	-	15
	289.5	296.0	4	0.092	-	-	15
	296.0	299.0	4	0.092	-	-	20
	299.0	300.0	4	0.092	-	-	5
	300.0	305.5	4	-	-	-	5
	305.5	309.4	2	-	-	-	1
	309.4	322.0	2	-	-	-	2
	322.0	322.6	2	0.960	-	-	2
	322.6	327.0	2	0.960	-	-	15
	327.0	327.5	2	-	-	-	15
	327.5	333.7	2	-	-	-	10
	333.7	333.8	2	-	f	-	10
	333.8	335.0	2	-	-	-	10
	335.0	340.5	2	-	-	-	2
	340.5	342.2	2	-	-	-	70
	342.2	371.5	1	-	f	-	4
	371.5	371.6	1	-	-	-	4
	371.6	372.0	1	-	f	-	4
	372.0	372.1	1	-	-	-	4
	372.1	373.1	1	-	f	-	4
	373.1	373.9	1	-	-	-	4
	373.9	376.5	1	-	f	-	4
	376.5	376.6	1	-	-	-	4
	376.6	376.7	1	-	f	-	4
	376.7	379.0	1	-	-	-	2
	379.0	381.2	1	-	f	-	1
	381.2	381.3	1	-	-	-	1
	381.3	390.0	1	-	f	-	1
	390.0	399.0	1	-	-	-	1
	399.0	401.0	1	-	f	qs	1
	401.0	410.0	1	-	f	-	1
BC2K-39							
	0.0	48.0	0	-	-	-	0
	48.0	53.0	5b	-	-	-	0.5
	53.0	68.5	5	-	-	-	2
	68.5	68.6	5	-	f	-	2
	68.6	69.0	5	-	-	-	2
	69.0	72.5	2	-	-	-	3

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	72.5	72.7	5	-	f	-	0.1
	72.7	79.5	5	-	-	-	0.1
	79.5	80.0	5	-	f	-	0.1
	80.0	82.5	5	-	-	-	0.1
	82.5	83.3	5	-	f	-	0.1
	83.3	97.5	5	-	-	-	0.1
	97.5	98.1	10	-	-	qv	0.1
	98.1	102.5	5	-	-	-	0.1
	102.5	117.0	2	-	-	-	1
	117.0	118.5	2	-	f	-	1
	118.5	118.9	10	-	f	qv	1
	117.0	121.1	2	-	f	-	1
	121.1	129.0	2	-	f	-	10
	129.0	130.0	2	-	f	-	1
	130.0	132.2	6	-	f	-	1
	132.2	147.8	6	-	-	-	1
	147.8	148.0	6	-	f	-	4
	148.0	159.5	6	-	-	-	4
	159.5	164.6	6	-	-	-	2
	164.6	164.7	6	-	f	-	2
	164.7	171.7	6	-	-	-	2
	171.7	174.7	6	-	f	-	2
	174.7	183.8	6	-	-	-	2
	183.8	188.5	7	-	-	-	5
	188.5	199.2	6	-	-	-	1
	199.2	199.5	6	-	f	-	1
	199.5	212.0	2	-	-	-	1
	212.0	213.4	3	-	-	-	0.5
	213.4	215.0	3	-	f	-	0.5
	215.0	220.0	3	-	-	-	0.5
	220.0	230.0	3	-	f	-	0.5
	230.0	250.0	3	-	-	-	0.5
	250.0	252.4	3	-	f	-	0.5
	252.4	262.5	3	-	-	-	0.5
	262.5	263.1	3	-	f	-	0.5
	263.1	266.0	3	-	-	-	0.5
	266.0	266.7	9	-	-	-	5
	266.7	267.4	9	-	f	-	5
	267.4	273.0	9	-	-	-	5
	273.0	273.1	9	-	f	-	5
	273.1	275.0	9	-	-	-	5
	275.0	275.6	10	-	f	qv	5
	275.6	276.0	9	-	-	-	5
	276.0	298.0	9	-	-	-	4
	298.0	320.0	9	-	-	-	2
	320.0	371.3	9	-	-	-	4
	371.3	371.5	9	-	f	-	10
	371.5	374.0	9	-	-	-	2
	374.0	374.5	9	-	f	-	2
	374.5	377.8	9	-	-	-	2
	377.8	378.0	9	-	f	-	2
	378.0	379.0	1	-	f	-	2
	379.0	385.5	1	-	f	-	1
	385.5	388.4	1	-	f	-	5
	388.4	410.0	1	-	f	-	1

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
BC2K-40							
	0.0	80.0	0	-	-	-	0
	80.0	110.4	3a	-	-	-	5
	110.4	126.0	2	-	-	-	3
	126.0	127.5	3a	-	-	-	3
	127.5	127.8	3a	-	f	-	3
	127.8	128.5	3a	-	-	-	3
	128.5	128.6	3a	-	f	-	3
	128.6	139.8	3a	-	-	-	3
	139.8	140.0	10	-	-	qv	1
	140.0	142.2	3a	-	-	-	3
	142.2	142.8	10	-	-	qv	5
	142.8	144.1	3a	-	-	-	5
	144.1	144.8	10	-	-	qv	5
	144.8	146.3	3a	-	-	-	5
	146.3	146.5	10	-	-	qv	5
	146.5	150.0	3a	-	-	-	10
	150.0	153.5	3a	-	-	-	5
	153.5	162.8	1	-	-	-	7
	162.8	164.0	3	-	-	-	15
	164.0	174.5	1	-	-	-	5
	174.5	175.2	1	-	f	-	10
	175.2	198.5	1	-	-	-	0.5
	198.5	245.5	3	-	-	qs	5
	245.5	255.8	3	-	f	qs	1
	255.8	257.8	10	-	f	qv	1
	257.8	258.2	10	-	-	qv	1
	258.2	263.0	3	-	-	qs	1
	263.0	267.0	10	-	-	qv	2
	267.0	270.0	10	-	-	qv	10
	270.0	280.6	2	-	-	qs	2
	280.6	282.0	2	-	-	-	2
	282.0	293.2	3	-	-	-	2
	293.2	310.8	1	-	-	-	1
	310.8	314.0	1	-	f	-	2
	314.0	314.6	1	-	f	-	3
	314.6	315.6	1	-	f	-	5
	315.6	323.0	10	-	f	qv	1
	323.0	323.5	1	-	f	-	1
	323.5	337.0	1	-	f	-	1
	337.0	343.0	1	-	-	-	1
	343.0	362.0	3a	-	-	-	0.5
	362.0	396.0	1	-	-	-	0.5
	396.0	398.2	10	-	f	qv	0.5
	398.2	407.0	1	-	-	-	0.5
	407.0	410.0	1	-	f	-	0.5
	410.0	411.1	1	-	-	-	0.5
	411.1	413.7	2	-	-	-	1
	413.7	415.0	1	-	-	-	0.5
	415.0	415.4	1	-	f	-	0.5
	415.4	418.0	1	-	-	-	0.5
	418.0	418.1	1	-	f	-	0.5
	418.1	425.0	1	-	-	-	0.5
	425.0	427.0	2	-	-	-	0.5

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
BC2K-41							
	0.0	28.0	0	-	-	-	0
	28.0	55.0	5ab	-	-	-	1
	55.0	55.4	5ab	-	f	-	1
	55.4	70.0	5ab	-	-	-	1
	70.0	70.3	5ab	-	f	-	1
	70.3	101.9	5ab	-	-	-	1
	101.9	102.7	5ab	-	f	-	1
	102.7	120.7	5ab	-	-	-	1
	120.7	139.1	5	-	-	-	1
	139.1	139.9	5	-	f	-	1
	139.9	150.3	5	-	-	-	1
	150.3	202.0	5a	-	-	-	0.5
	202.0	203.8	5a	-	-	qs	5
	203.8	206.0	5a	-	-	-	5
	206.0	239.2	5a	-	-	-	0.5
	239.2	239.6	5a	-	f	-	0.5
	239.6	242.1	5a	-	-	-	0.5
	242.1	243.5	5a	-	f	-	0.5
	243.5	246.5	5a	-	-	-	0.5
	246.5	247.0	5a	-	f	-	0.5
	247.0	248.8	5a	-	-	-	0.5
	248.8	249.0	5a	-	f	-	0.5
	249.0	268.8	5a	-	-	-	0.5
	268.8	269.1	5a	-	f	-	0.5
	269.1	270.0	5a	-	-	-	0.5
	270.0	298.0	5	-	-	-	0.5
	298.0	301.0	5	-	f	-	1
	301.0	343.7	5	-	-	-	0.5
	343.7	346.2	10	-	-	qv	5
	346.2	349.7	5	-	-	-	0.5
	349.7	350.0	5	-	f	-	0.5
	350.0	357.5	5	-	-	-	0.5
	357.5	360.0	5	-	f	-	0.5
	360.0	365.0	5	-	-	-	0.5
	365.0	385.5	5	-	f	-	0.5
	385.5	387.0	5	-	-	-	0.5
BC2K-42							
	0.0	10.0	0	-	-	-	0
	10.0	17.0	5	-	-	-	0.5
	17.0	25.0	5a	-	-	-	0.5
	25.0	36.6	5	-	-	-	0.5
	36.6	39.5	5	-	-	-	5
	39.5	63.0	5	-	-	-	0.5
	63.0	89.0	5a	-	-	-	2
	89.0	130.0	5	-	-	-	2
	130.0	133.0	5	-	f	-	2
	133.0	134.7	10	0.083	-	qv	2
	134.7	141.5	2	-	-	-	2
	141.5	143.3	2	0.088	-	-	2
	143.3	145.0	5	0.088	-	-	2
	145.0	150.0	5	-	-	-	2
	150.0	150.1	5	-	f	-	2

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	150.1	153.6	5	-	-	-	2
	153.2	153.4	5	-	f	-	2
	153.4	153.6	5	-	-	-	2
	153.6	154.3	5	0.333	-	-	2
	154.3	154.4	5	0.333	f	-	2
	154.4	155.0	5	0.333	-	-	2
	155.0	157.7	10	0.333	-	qv	2
	157.7	157.8	10	0.333	f	qv	2
	157.8	158.0	10	0.333	-	qv	2
	158.0	158.1	2	0.333	f	-	2
	158.1	158.5	2	0.333	-	-	2
	158.5	165.8	2	0.030	-	-	2
	165.8	169.0	2	-	-	-	2
	169.0	169.5	2	-	f	-	2
	169.5	188.0	1	-	-	-	1
	188.0	189.3	1	-	-	qs	1
	189.3	222.5	2	-	-	qs	2
	222.5	284.5	6	-	-	-	2
	284.5	333.5	2	-	-	-	2
	333.5	334.6	10	-	-	qv	2
	334.6	357.0	2	-	-	-	2
	357.0	421.0	6	-	-	-	0.5
	421.0	422.8	2	-	-	-	3
	422.8	423.4	2	-	f	-	0.5
	423.4	443.0	6	-	-	-	0.5
	443.0	445.0	6	-	f	-	0.5
	445.0	455.0	6	-	-	-	0.5
	455.0	471.0	2	-	-	-	0.5
	471.0	474.5	2	-	f	-	5
	474.5	484.0	2	-	f	-	1
	484.0	488.0	2	-	f	-	4
	488.0	520.0	3	-	-	-	0.5
BC2K-43							
	0.0	16.0	0	-	-	-	0
	16.0	31.5	10	-	-	qv	0.5
	31.5	32.2	10	0.215	-	qv	0.5
	32.2	32.4	10	0.030	-	qv	0.5
	32.4	34.0	2	0.030	-	qs	0.5
	34.0	40.0	2	0.030	-	-	0.5
	40.0	41.3	2	-	-	-	0.5
	41.3	42.1	2	-	f	-	0.5
	42.1	62.3	10	-	-	qv	0.5
	62.3	62.6	2	-	-	-	4
	62.6	65.0	10	-	-	qv	4
	65.0	66.0	2	-	-	-	4
	66.0	67.0	10	-	-	qv	4
	67.0	68.8	2	-	-	-	4
	68.8	79.5	10	-	-	qv	4
	79.5	85.0	2	-	-	-	6
	85.0	87.0	2	-	-	-	2
	87.0	87.1	2	-	f	-	2
	87.1	97.5	2	-	-	-	2
	97.5	97.6	2	-	f	-	2
	97.6	146.5	2	-	-	-	2

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	146.5	147.0	10	-	-	qv	2
	147.0	147.1	10	-	f	qv	2
	147.1	147.5	10	-	-	qv	2
	147.5	148.0	2	-	-	-	2
	148.0	149.5	10	-	f	qv	2
	149.5	149.6	10	-	-	qv	2
	149.6	156.0	2	-	f	-	2
	156.0	165.0	1	-	-	-	1
	165.0	165.1	1	-	f	-	1
	165.1	167.2	1	-	-	-	1
	167.2	220.0	1	-	-	qs	2
	220.0	220.1	1	-	f	qs	2
	220.1	225.0	1	-	-	qs	2
	225.0	225.1	1	-	f	qs	2
	225.1	227.0	1	-	-	qs	2
	227.0	233.0	1	-	-	-	3
	233.0	243.0	7	-	-	-	5
	243.0	276.1	3	-	-	qs	10
	276.1	279.0	1	-	-	-	4
	279.0	279.6	1	-	f	-	4
	279.6	281.2	1	-	-	-	4
	281.2	289.5	1	-	f	-	4
	289.5	293.3	1	-	-	-	4
	293.3	417.3	1	-	-	qs	1
	417.3	418.3	1	-	f	qs	1
	418.3	434.0	1	-	-	qs	1
	434.0	530.0	1	-	-	-	2
BC2K-44							
	0.0	10.0	0	-	-	-	0
	10.0	44.0	10	-	-	qv	0
	44.0	45.0	10	-	f	qv	0
	45.0	50.0	10	-	-	qv	0
	50.0	52.0	10	-	f	qv	0
	52.0	90.2	10	-	-	qv	0
	90.2	93.5	2	-	-	-	2
	93.5	95.5	10	-	-	qv	2
	95.5	96.5	10	0.409	-	qv	2
	96.5	96.9	10	0.031	-	qv	2
	96.9	99.5	10	-	-	qv	2
	99.5	100.6	10	0.043	-	qv	2
	100.6	102.8	10	-	-	qv	2
	102.8	103.3	10	0.615	-	qv	2
	103.3	113.3	2	0.025	-	-	2
	113.3	118.4	2	-	-	-	2
	118.4	119.5	10	0.195	-	qv	2
	119.5	121.7	10	-	-	qv	2
	121.7	127.0	2	-	-	-	2
	127.0	142.2	6	-	-	-	2
	142.2	142.7	1	-	f	-	2
	142.7	155.1	1	-	-	-	2
	155.1	163.5	6	-	-	-	2
	163.5	163.6	10	-	-	qv	2
	163.6	164.0	6	-	-	-	2
	164.0	166.2	2	-	-	-	2

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	166.2	166.5	10	-	-	qv	2
	166.5	167.2	2	-	-	-	2
	167.2	193.2	1	-	-	qs	0.5
	189.0	190.0	1	-	f	qs	0.5
	190.0	193.2	1	-	-	qs	0.5
	193.2	220.0	1	-	-	qs	3
	220.0	227.0	9	-	-	qs	20
	227.0	232.2	9	-	-	qs	20
	232.2	235.6	9	-	-	qs	20
	235.6	236.2	9	-	-	qs	20
	236.2	242.0	2	-	-	qs	1
	242.0	249.5	3	-	-	qs	1
	249.5	266.0	7	-	-	qs	3
	266.0	266.1	1	-	f	qs	1
	266.1	298.2	1	-	-	qs	1
	298.2	303.5	1	-	f	qs	0.5
	303.5	335.0	1	-	-	qs	0.5
	335.0	336.5	1	-	f	qs	0.5
	336.5	337.0	1	-	-	qs	0.5
	337.0	344.0	1	-	-	qs	2
	344.0	370.0	1	-	-	qs	1
BC2K-45							
	0.0	10.0	0	-	-	-	0
	10.0	30.2	2	-	-	-	5
	30.2	35.0	2	-	f	qs	4
	35.0	45.0	2	0.018	f	qs	3
	45.0	47.5	2	-	f	qs	3
	47.5	47.9	10	-	f	qv	0
	47.9	50.5	10	-	f	qv	2
	50.5	66.5	2	-	-	-	4
	66.5	89.0	10	-	-	qv	2
	89.0	90.0	10	-	-	qv	10
	90.0	157.7	10	-	-	qv	0.5
	157.7	158.8	10	-	f	qv	0.5
	158.8	160.0	10	-	-	qv	0.5
	160.0	174.7	2	-	-	-	12
	174.7	175.4	2	-	f	-	12
	175.4	181.4	6	-	-	-	2
	181.4	182.1	6	-	f	-	2
	182.1	189.8	6	-	-	-	2
	189.8	201.0	3a	-	-	-	2
	201.0	227.0	1	-	-	-	1
	227.0	260.0	1	-	-	-	2
	260.0	265.0	2	-	-	qs	3
	265.0	270.0	2	-	-	qs	5
	270.0	273.6	2	-	-	qs	3
	273.6	286.0	3a	-	-	-	3
	286.0	291.5	3	-	-	qs	2
	291.5	296.0	6	-	-	-	2
	296.0	300.0	6	-	-	-	2
	300.0	305.0	6	-	-	-	2
	305.0	309.5	6	-	-	-	2
	309.5	310.0	3a	-	-	-	0.5
	310.0	315.0	3a	-	-	-	0.5

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	315.0	320.0	3a	-	-	-	0.5
	320.0	321.0	3a	-	-	-	0.5
	321.0	375.4	6	-	-	-	3
	373.7	375.4	6	-	f	-	3
	375.4	375.6	6	-	f	-	5
	375.6	380.0	2	-	-	-	1
	380.0	396.0	2	-	-	-	4
	393.3	394.3	2	-	f	-	4
	394.3	396.0	2	-	-	-	4
	396.0	396.8	2	-	f	-	4
	396.8	397.9	10	-	-	qv	4
	397.9	438.0	2	-	-	-	4
	438.0	460.6	6	-	-	-	1
	460.6	466.5	3	-	-	-	1
	466.5	468.5	3	-	f	-	1
	468.5	469.7	3	-	-	-	1
	469.7	470.2	3	-	f	-	1
	470.2	508.0	3	-	-	-	1
	508.0	521.2	2	-	-	-	2
	521.2	524.0	6	-	-	-	1
	524.0	524.1	10	-	-	qv	1
	524.1	541.4	6	-	-	-	1
	541.4	546.0	6	-	-	qs	1
	546.0	567.8	6	-	-	-	1
	567.8	571.0	6	-	-	qs	5
	571.0	608.2	6	-	-	-	1
	608.2	609.0	6	-	f	-	1
	609.0	609.2	6	-	-	-	1
	609.2	616.6	6	-	-	qs	1
	616.6	619.0	2	-	-	-	1
	619.0	661.4	6	-	-	-	0.5
	661.4	670.0	6	-	-	-	4
BC2K-46							
	0.0	20.0	0	-	-	-	0
	20.0	45.0	5	-	-	-	0.5
	45.0	93.0	2	-	-	-	2
	93.0	119.0	5	-	-	-	0.5
	119.0	175.3	2	-	-	-	2
	175.3	177.0	2	-	f	-	2
	177.0	190.0	2	-	-	-	2
	190.0	191.0	5	-	-	-	1
	191.0	195.0	5	-	f	-	1
	195.0	204.9	5	-	-	-	1
	204.9	222.0	2	-	-	-	2
	222.0	275.5	6	-	-	-	2
	275.5	276.0	6	-	-	-	10
	276.0	279.2	6	-	-	-	2
	279.2	285.0	2	-	-	-	3
	285.0	286.5	1	-	-	qs	3
	286.5	290.0	1	-	-	-	1
	290.0	291.0	1	-	-	qs	1
	291.0	328.0	1	-	-	-	1
	328.0	330.5	2	-	-	-	10
	330.5	330.7	2	-	f	-	10

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	330.7	331.5	2	-	-	-	10
	331.5	333.4	2	-	-	-	30
	333.4	333.6	2	-	f	-	20
	333.6	344.2	2	-	-	-	10
	341.5	344.3	2	-	f	-	10
	344.3	345.0	10	-	f	qv	10
	345.0	346.7	10	-	-	qv	10
	346.5	346.7	10	-	f	qv	0.5
	346.7	380.2	1	-	f	-	0.5
	380.2	415.7	1	-	-	qs	1
	415.7	415.9	1	-	f	qs	1
	415.9	435.0	1	-	-	qs	1
	435.0	445.0	1	-	f	qs	1
BC2K-47							
	0.0	34.0	0	-	-	-	0
	34.0	61.0	1	-	-	-	0.5
	61.0	67.5	9	-	-	-	7
	67.5	67.6	9	-	f	-	7
	67.6	69.0	9	-	-	-	7
	69.0	69.2	9	-	f	-	7
	69.2	71.5	9	-	-	-	7
	71.5	72.2	9	-	f	-	7
	72.2	73.2	9	-	-	-	7
	73.2	73.5	9	-	f	-	7
	73.5	73.7	9	-	-	-	7
	73.7	74.6	9	-	f	-	7
	74.6	77.0	9	-	-	-	7
	77.0	83.1	2	-	-	-	3
	83.1	86.9	6	-	-	-	0.5
	86.9	87.1	6	-	f	-	0.5
	87.1	93.5	6	-	-	-	0.5
	93.5	93.7	6	-	f	-	0.5
	93.7	126.5	6	-	-	-	0.5
	126.5	128.0	6	-	f	-	0.5
	128.0	155.8	6	-	-	-	0.5
	155.8	199.0	3	-	-	-	0.5
	168.9	170.7	3	-	-	-	10
	170.7	174.6	3	-	-	-	0.5
	174.6	175.6	3	-	-	-	2
	175.6	199.0	3	-	-	-	0.5
	199.0	199.1	3	-	f	-	0.5
	199.1	202.5	3	-	-	-	0.5
	202.5	204.0	9	-	-	-	12
	204.0	207.0	9	-	-	-	12
	207.0	207.1	10	-	-	qv	12
	207.1	209.0	9	-	-	-	12
	209.0	210.8	3	-	-	-	10
	210.8	210.9	10	-	-	qv	10
	210.9	214.0	3	-	-	-	10
	214.0	216.0	3	0.069	-	-	10
	216.0	216.2	10	0.069	-	qv	10
	216.2	219.0	3	0.069	-	-	10
	219.0	221.0	3	0.155	-	-	10
	221.0	222.0	10	0.155	-	qv	10

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	222.0	222.2	10	0.031	-	qv	10
	222.2	224.2	3	0.031	-	"	10
	224.2	224.8	3	-	-	"	10
	224.8	225.0	2	-	f	"	0
	225.0	246.3	2	-	-	"	0
	246.3	248.8	7	-	-	"	10
	248.8	249.3	7	-	f	"	10
	249.3	250.0	7	-	-	"	10
	250.0	255.2	1	-	-	"	8
	255.2	260.0	1	-	-	-	3
	260.0	279.3	1	-	-	-	1
	279.3	280.2	1	-	-	-	2
	280.2	301.2	1a	-	-	-	1.5
	301.2	302.2	10	-	-	qv	3
	302.2	310.0	1a	-	-	-	1.5
	310.0	315.0	1a	-	-	-	1.5
	315.0	320.0	1a	-	-	-	1.5
	320.0	322.8	1a	-	-	-	1.5
	322.8	323.5	10	-	-	qv	1.5
	323.5	330.1	1	-	-	-	0
	330.1	330.2	10	-	-	qv	3
	330.2	333.9	1	-	-	qs	3
	333.9	334.0	10	-	-	qv	3
	334.0	358.4	1	-	-	-	1
	358.4	370.0	1	-	-	qs	1
	370.0	379.0	1	-	-	-	1
	379.0	385.0	3	-	f	-	0
	385.0	390.0	3	-	-	-	0
	390.0	391.0	3	-	f	-	0
	391.0	400.0	3	-	-	-	0
BC2K-48							
	0.0	30.0	0	-	-	-	0
	30.0	42.8	2	-	-	qs	1
	42.8	43.8	2	-	-	qs	10
	43.8	52.0	2	-	-	qs	1
	52.0	58.0	3	-	-	-	1
	58.0	58.6	3	-	f	-	1
	58.6	59.3	3	-	-	-	1
	59.3	59.4	3	-	f	-	1
	59.4	61.7	3	-	-	-	1
	61.7	80.0	2	-	-	-	3
	80.0	81.8	2	-	-	-	0
	81.8	82.3	2	-	f	-	0
	82.3	83.3	2	-	-	-	0
	83.3	104.5	6	-	-	-	2
	104.5	104.8	10	-	-	qv	2
	104.8	138.9	6	-	-	-	2
	138.9	140.0	10	-	-	qv	2
	140.0	143.6	6	-	-	-	2
	143.6	147.5	6	-	-	-	7
	147.5	152.2	6	-	-	-	2
	152.2	158.5	3	-	-	-	3
	158.5	162.1	3a	-	-	-	5
	162.1	162.3	3a	-	f	-	3

HOLE	FROM	TO	ROCK CODE	INTERCEPT (oz/st)	FAULT	VEIN STRINGER	PYRITE (%)
	162.3	181.6	3a	-	-	-	3
	181.6	182.4	3a	-	-	-	15
	182.4	238.4	3a	-	-	-	3
	238.4	246.2	7	-	-	-	3
	246.2	251.0	7	-	-	-	5
	251.0	255.0	7	-	-	-	10
	251.0	259.0	7	-	-	-	10
	259.0	265.0	7	-	-	-	5
	265.0	268.0	7	-	-	-	5
	268.0	272.5	7	-	-	-	5
	272.5	290.0	8	-	-	-	15
	290.0	292.0	8	-	-	-	15
	292.0	293.0	8	-	-	-	50
	293.0	294.5	8	-	-	-	15
	294.5	295.0	8	-	-	-	50
	295.0	310.0	8	-	-	-	15
	310.0	315.5	8	-	-	-	15
	315.5	320.0	8	-	-	-	10
	320.0	326.0	8	-	-	-	10
	326.0	329.5	8	-	-	-	50
	329.5	333.0	7	-	-	-	3
	333.0	335.5	8	-	-	-	15
	335.5	347.0	7	-	-	-	3
	347.0	353.0	2	-	-	qs	5
	353.0	356.0	2	-	f	qs	3
	356.0	377.7	2	-	-	qs	3
	377.7	386.0	2	-	f	qs	3
	386.0	401.5	2	-	f	qs	7
	401.5	405.0	2	-	f	qs	5

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-03	125.0	135.0	0.050	169094	A00659
BC2K-03	135.0	145.0	0.312	169095	
BC2K-03	185.5	187.0	0.003	169096	
BC2K-03	210.0	214.5	0.030	169097	
BC2K-03	214.5	220.0	0.140	169098	
BC2K-03	220.0	225.0	0.114	169099	
BC2K-03	225.0	234.5	0.553	169100	
BC2K-03	234.5	240.0	0.014	169101	
BC2K-04	110.0	112.0	0.002	169624	A000958
BC2K-04	112.0	119.8	0.001	169625	A000825
BC2K-04	119.8	125.0	0.126	169626	A000659
BC2K-04	142.0	145.0	0.071	169102	
BC2K-04	145.0	150.0	0.877	169103	
BC2K-04	150.0	155.0	0.199	169104	
BC2K-04	155.0	160.0	0.460	169105	
BC2K-04	160.0	165.0	0.044	169106	
BC2K-04	165.0	170.0	0.030	169107	
BC2K-04	170.0	175.0	0.051	169725	
BC2K-04	175.0	178.6	0.050	169726	
BC2K-04	178.6	185.0	0.012	169727	
BC2K-04	185.0	190.0	0.023	169728	
BC2K-04	190.0	195.0	0.010	169729	
BC2K-04	195.0	200.0	0.007	169730	
BC2K-08	50.0	52.0	0.095	169601	A000958
BC2K-08	89.4	94.5	0.020	169602	A000825
BC2K-08	94.5	99.0	0.238	169603	
BC2K-08	99.0	105.0	0.084	169604	
BC2K-08	105.0	110.0	0.193	169605	
BC2K-08	110.0	112.0	0.002	169606	
BC2K-08	112.0	124.0	0.003	169607	
BC2K-08	124.0	134.0	0.001	169608	
BC2K-08	134.0	140.8	0.006	169609	
BC2K-08	140.8	147.0	0.003	169610	
BC2K-08	147.0	153.0	0.003	169611	
BC2K-08	153.0	160.0	0.003	169612	
BC2K-08	160.0	164.8	0.032	169613	
BC2K-08	164.8	168.0	0.079	169614	
BC2K-08	168.0	169.9	0.004	169615	
BC2K-08	169.9	175.6	0.073	169616	
BC2K-08	175.6	178.9	0.001	169617	
BC2K-08	178.9	185.4	0.005	169618	
BC2K-08	205.0	207.0	0.002	169619	
BC2K-08	207.0	210.2	0.014	169620	
BC2K-08	210.2	215.0	0.967	169621	
BC2K-08	215.0	221.8	0.302	169622	
BC2K-08	221.8	228.9	0.160	169623	
BC2K-08	228.9	235.0	0.005	169720	
BC2K-08	235.0	240.0	0.014	169721	
BC2K-08	240.0	245.0	0.004	169722	
BC2K-08	245.0	250.0	0.000	169723	
BC2K-08	250.0	255.0	0.001	169724	
BC2K-09	19.0	25.0	0.001	169475	A001127
BC2K-09	35.0	40.0	0.016	169476	
BC2K-09	40.0	45.0	0.012	169477	
BC2K-09	70.0	75.0	0.009	169478	
BC2K-09	75.0	77.5	0.017	169479	
BC2K-09	77.5	84.0	0.207	169480	
BC2K-09	84.0	92.0	0.002	169481	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-09	92.0	100.7	0.005	169482	
BC2K-09	100.7	101.5	0.033	169483	
BC2K-09	101.5	102.3	1.583	169484	
BC2K-09	102.3	111.8	0.047	169485	
BC2K-09	111.8	118.9	0.063	169486	
BC2K-09	118.9	126.8	0.012	169487	
BC2K-09	126.8	134.0	0.047	169488	
BC2K-09	134.0	140.0	0.007	169489	
BC2K-09	140.0	149.6	0.006	169490	
BC2K-09	149.6	152.4	0.002	169491	
BC2K-09	152.4	160.8	0.001	169492	
BC2K-09	160.8	165.8	0.001	169493	
BC2K-09	165.8	172.6	0.001	169494	
BC2K-09	172.6	177.6	0.001	169495	
BC2K-09	177.6	180.8	0.001	169496	
BC2K-09	180.8	190.0	0.001	169497	
BC2K-09	190.0	198.2	0.001	169498	
BC2K-09	198.2	205.0	0.000	169499	
BC2K-09	205.0	213.3	0.001	169500	
BC2K-09	213.3	220.0	0.000	169786	
BC2K-09	220.0	230.2	0.000	169787	
BC2K-09	230.2	236.7	0.000	169788	
BC2K-09	236.7	245.7	0.000	169789	
BC2K-09	245.7	252.0	0.000	169790	
BC2K-09	252.0	256.0	0.001	169791	
BC2K-09	256.0	265.0	0.015	169792	
BC2K-09	265.0	270.0	0.000	169793	
BC2K-09	270.0	276.6	0.000	169794	
BC2K-09	276.6	285.0	0.000	169795	
BC2K-09	285.0	293.0	0.000	169796	
BC2K-09	293.0	300.0	0.000	169797	
BC2K-09	300.0	308.0	0.000	169798	
BC2K-09	308.0	315.8	0.000	169799	
BC2K-09	315.8	326.2	0.000	169800	
BC2K-09	326.2	333.4	0.000	169801	
BC2K-09	333.4	341.0	0.000	169802	
BC2K-09	341.0	351.0	0.000	169803	
BC2K-09	351.0	361.0	0.000	169804	
BC2K-09	361.0	367.6	0.000	169805	
BC2K-09	367.6	376.1	0.000	169806	
BC2K-09	376.1	385.6	0.000	169807	
BC2K-09	385.6	395.0	0.000	169808	
BC2K-10	105.0	107.5	0.003	169731	A001008
BC2K-10	107.5	112.7	0.001	169732	
BC2K-10	112.7	117.3	0.000	169733	
BC2K-10	117.3	127.5	0.000	169734	
BC2K-10	127.5	129.2	0.000	169735	
BC2K-10	129.2	134.0	0.003	169736	
BC2K-10	134.0	142.4	0.003	169737	
BC2K-10	142.4	150.0	0.001	169738	
BC2K-10	150.0	155.6	0.005	169739	
BC2K-10	155.6	157.3	0.013	169740	
BC2K-10	157.3	157.9	0.001	169741	
BC2K-10	157.9	160.3	0.286	169742	
BC2K-10	160.3	166.4	0.074	169743	
BC2K-10	166.4	177.3	0.190	169744	
BC2K-10	177.3	187.0	0.065	169745	
BC2K-10	187.0	196.1	0.112	169746	
BC2K-10	196.1	200.2	0.487	169747	
BC2K-10	200.2	202.8	2.237	169748	
BC2K-10	202.8	211.5	2.540	169749	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-10	211.5	214.4	0.768	169750	
BC2K-10	214.4	216.0	0.699	169751	
BC2K-10	216.0	221.0	0.479	169752	
BC2K-10	221.0	229.0	1.076	169753	
BC2K-10	229.0	235.0	0.991	169754	
BC2K-10	235.0	240.6	0.984	169755	
BC2K-10	240.6	242.6	0.162	169756	
BC2K-10	242.6	250.8	0.022	169757	
BC2K-10	250.8	255.3	0.003	169758	
BC2K-10	255.3	260.0	0.003	169759	
BC2K-10	260.0	267.1	0.002	169760	
BC2K-10	267.1	270.6	0.001	169761	
BC2K-10	270.6	277.3	0.001	169762	
BC2K-10	277.3	288.0	0.001	169763	
BC2K-10	288.0	299.5	0.004	169764	
BC2K-10	299.5	300.1	0.011	169765	
BC2K-10	300.1	305.0	0.060	169766	
BC2K-10	305.0	311.3	0.151	169767	
BC2K-10	311.3	312.4	0.440	169768	
BC2K-10	312.4	320.0	0.019	169769	
BC2K-10	320.0	322.0	0.042	169770	
BC2K-10	322.0	330.0	0.139	169771	
BC2K-10	330.0	335.0	0.013	169772	
BC2K-10	335.0	342.5	0.036	169773	
BC2K-10	342.5	348.6	0.033	169774	
BC2K-10	348.6	350.0	0.024	169775	
BC2K-10	350.0	359.0	0.006	169776	
BC2K-10	359.0	361.2	0.035	169777	
BC2K-10	361.2	363.4	0.017	169778	
BC2K-10	363.4	370.0	0.009	169779	
BC2K-10	370.0	375.7	0.004	169780	
BC2K-10	375.7	377.1	0.002	169781	
BC2K-10	377.1	379.7	0.006	169782	
BC2K-10	379.7	382.7	0.021	169783	
BC2K-10	382.7	387.0	0.004	169784	
BC2K-10	387.0	395.0	0.005	169785	
BC2K-11	56.0	60.0	0.028	169627	A000958
BC2K-11	98.0	105.0	0.020	169628	
BC2K-11	165.0	173.3	0.001	169629	
BC2K-11	173.3	181.9	0.014	169630	
BC2K-11	181.9	186.2	0.058	169631	
BC2K-11	186.2	190.0	0.053	169632	
BC2K-11	190.0	197.6	0.221	169633	
BC2K-11	197.6	198.9	0.010	169634	
BC2K-11	248.0	254.5	0.002	169635	
BC2K-11	254.5	259.6	0.001	169636	
BC2K-11	259.6	261.8	0.000	169637	
BC2K-11	261.8	270.0	0.000	169638	
BC2K-11	270.0	275.0	0.000	169639	
BC2K-11	275.0	281.0	0.000	169640	
BC2K-11	281.0	288.5	0.000	169641	
BC2K-11	288.5	306.0	0.000	169642	
BC2K-11	306.0	314.5	0.000	169643	
BC2K-11	314.5	320.0	0.000	169644	
BC2K-11	320.0	389.8	0.000	169645	
BC2K-11	389.8	393.0	0.000	169646	
BC2K-11	393.0	398.0	0.000	169647	
BC2K-11	398.0	405.0	0.000	169648	
BC2K-11	405.0	415.0	0.000	169649	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-11	415.0	420.0	0.000	169650	
BC2K-11	420.0	426.8	0.000	169651	
BC2K-11	426.8	434.3	0.000	169652	
BC2K-11	434.3	440.0	0.000	169653	
BC2K-11	440.0	445.3	0.000	169654	
BC2K-11	445.3	454.0	0.000	169655	
BC2K-11	454.0	458.1	0.000	169656	
BC2K-11	458.1	461.1	0.000	169657	
BC2K-11	461.1	464.8	0.000	169658	
BC2K-11	464.8	473.5	0.000	169659	
BC2K-12	182.5	184.9	0.098	169701	A000960
BC2K-12	184.9	190.0	0.074	169702	
BC2K-12	190.0	195.5	0.062	169703	
BC2K-12	195.5	199.3	0.007	169704	
BC2K-12	199.3	204.6	0.347	169705	
BC2K-12	204.6	209.0	0.865	169706	
BC2K-12	209.0	214.5	1.337	169707	
BC2K-12	214.5	217.6	0.997	169708	
BC2K-12	217.6	225.0	1.159	169709	
BC2K-12	225.0	235.0	0.402	169710	
BC2K-12	235.0	240.5	0.186	169711	
BC2K-12	240.5	242.2	0.006	169712	
BC2K-12	242.2	243.7	0.876	169713	
BC2K-12	243.7	245.6	0.298	169714	
BC2K-12	245.6	252.6	0.025	169715	
BC2K-12	252.6	257.0	0.734	169716	
BC2K-12	257.0	264.8	0.028	169717	
BC2K-12	264.8	270.0	0.006	169718	
BC2K-12	270.0	275.0	0.002	169719	
BC2K-12	362.6	375.0	0.008	169809	
BC2K-12	375.0	385.0	0.000	169810	
BC2K-12	385.0	395.0	0.000	169811	
BC2K-12	395.0	400.8	0.001	169812	
BC2K-12	400.8	406.6	0.000	169813	
BC2K-12	406.6	415.0	0.000	169814	
BC2K-12	415.0	425.0	0.000	169815	
BC2K-12	425.0	435.0	0.000	169816	
BC2K-12	435.0	445.0	0.000	169817	
BC2K-12	445.0	455.0	0.000	169818	
BC2K-12	455.0	465.0	0.000	169819	
BC2K-13	165.0	170.0	0.003	169401	A001077
BC2K-13	170.0	175.0	0.009	169402	
BC2K-13	175.0	180.0	0.004	169403	
BC2K-13	180.0	185.0	0.003	169404	
BC2K-13	185.0	190.0	0.011	169405	
BC2K-13	190.0	194.5	0.001	169406	
BC2K-13	194.5	200.0	0.002	169407	
BC2K-13	200.0	205.0	0.062	169408	
BC2K-13	205.0	210.0	0.001	169409	
BC2K-13	210.0	215.0	0.001	169410	
BC2K-13	215.0	220.0	0.000	169411	
BC2K-13	220.0	222.5	0.001	169412	
BC2K-13	222.5	226.0	0.001	169413	
BC2K-13	226.0	229.4	0.001	169414	
BC2K-13	229.4	235.0	0.000	169415	
BC2K-13	235.0	240.0	0.000	169416	
BC2K-13	240.0	241.0	0.010	169417	
BC2K-13	241.0	245.0	0.006	169418	
BC2K-13	245.0	250.0	0.324	169419	
BC2K-13	250.0	255.0	0.357	169420	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-13	255.0	260.0	0.054	169421	
BC2K-13	260.0	265.0	0.250	169422	
BC2K-13	265.0	270.0	0.150	169423	
BC2K-13	270.0	275.0	0.137	169424	
BC2K-13	275.0	280.0	0.008	169425	
BC2K-13	280.0	281.5	0.033	169426	
BC2K-13	281.5	283.5	0.514	169427	
BC2K-13	283.5	285.0	1.001	169428	
BC2K-13	285.0	290.0	1.068	169429	
BC2K-13	290.0	293.5	0.472	169430	
BC2K-13	293.5	295.0	0.060	169431	
BC2K-13	295.0	300.7	0.196	169432	
BC2K-13	300.7	305.0	0.122	169433	
BC2K-13	305.0	310.0	0.375	169434	
BC2K-13	310.0	315.0	1.163	169435	
BC2K-13	315.0	320.0	0.735	169436	
BC2K-13	320.0	325.0	0.076	169437	
BC2K-13	325.0	330.0	0.282	169438	
BC2K-13	330.0	332.0	0.012	169439	
BC2K-13	332.0	335.0	0.102	169440	
BC2K-13	335.0	340.0	0.088	169441	
BC2K-13	340.0	345.0	0.254	169442	
BC2K-13	345.0	350.0	0.109	169443	
BC2K-13	350.0	354.0	0.068	169444	
BC2K-13	354.0	359.0	0.016	169445	
BC2K-13	359.0	365.0	0.013	169446	
BC2K-13	365.0	370.0	0.003	169447	
BC2K-13	370.0	372.4	0.004	169448	
BC2K-13	372.4	375.0	0.006	169449	
BC2K-13	375.0	380.0	0.003	169450	
BC2K-13	380.0	382.6	0.003	169451	
BC2K-13	382.6	385.0	0.002	169452	
BC2K-13	385.0	390.0	0.001	169453	
BC2K-13	390.0	395.0	0.001	169454	
BC2K-13	395.0	400.0	0.001	169455	
BC2K-13	400.0	405.0	0.001	169456	
BC2K-13	405.0	411.9	0.001	169457	
BC2K-13	411.9	413.7	0.006	169458	
BC2K-13	413.7	419.3	0.001	169459	
BC2K-13	419.3	425.0	0.000	169460	
BC2K-13	425.0	430.0	0.000	169461	
BC2K-13	430.0	435.0	0.000	169462	
BC2K-13	435.0	440.0	0.000	169463	
BC2K-13	440.0	445.0	0.000	169464	
BC2K-13	445.0	450.0	0.000	169465	
BC2K-13	450.0	455.0	0.000	169466	
BC2K-13	455.0	460.0	0.000	169467	
BC2K-13	460.0	465.0	0.000	169468	
BC2K-13	465.0	467.5	0.001	169469	
BC2K-13	467.5	470.0	0.001	169470	
BC2K-13	470.0	475.0	0.001	169471	
BC2K-13	475.0	480.0	0.001	169472	
BC2K-13	480.0	482.8	0.001	169473	
BC2K-13	482.8	485.0	0.005	169474	
BC2K-14	105.0	110.0	0.001	169901	A001248
BC2K-14	110.0	115.0	0.000	169902	
BC2K-14	115.0	120.0	0.000	169903	
BC2K-14	120.0	125.0	0.001	169904	
BC2K-14	125.0	130.0	0.000	169905	
BC2K-14	130.0	135.0	0.000	169906	
BC2K-14	135.0	140.0	0.005	169907	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-14	215.7	218.3	0.000	169908	
BC2K-14	218.3	221.5	0.000	169909	
BC2K-14	221.5	225.0	0.000	169910	
BC2K-14	225.0	230.0	0.000	169911	
BC2K-14	230.0	236.0	0.001	169912	
BC2K-14	236.0	240.0	0.001	169913	
BC2K-14	240.0	245.0	0.000	169914	
BC2K-14	245.0	251.5	0.000	169915	
BC2K-14	251.5	255.0	0.000	169916	
BC2K-14	255.0	260.0	0.000	169917	
BC2K-14	260.0	265.0	0.001	169918	
BC2K-14	265.0	270.0	0.000	169919	
BC2K-14	270.0	276.5	0.000	169920	
BC2K-14	276.5	280.0	0.000	169921	
BC2K-14	280.0	285.0	0.000	169922	
BC2K-14	285.0	290.0	0.011	169923	
BC2K-14	290.0	295.0	0.049	169924	
BC2K-14	295.0	300.0	0.002	169925	
BC2K-14	300.0	305.0	0.001	169926	
BC2K-14	305.0	310.0	0.006	169927	
BC2K-14	310.0	315.0	0.011	169928	
BC2K-14	315.0	320.0	0.018	169929	
BC2K-14	320.0	325.0	0.003	169930	
BC2K-14	325.0	330.0	0.015	169931	
BC2K-14	330.0	335.0	0.008	169932	
BC2K-14	335.0	340.0	0.014	169933	
BC2K-14	340.0	344.5	0.002	169934	
BC2K-14	344.5	350.0	0.225	169935	
BC2K-14	350.0	355.0	0.105	169936	
BC2K-14	355.0	360.0	0.001	169937	
BC2K-14	360.0	365.0	0.025	169938	
BC2K-14	365.0	370.0	0.065	169939	
BC2K-14	370.0	375.0	0.066	169940	
BC2K-14	375.0	380.0	0.119	169941	
BC2K-14	380.0	385.0	0.098	169942	
BC2K-14	385.0	390.0	0.045	169943	
BC2K-14	390.0	395.0	0.024	169944	
BC2K-14	395.0	400.0	0.001	169945	
BC2K-14	400.0	405.0	0.007	169946	
BC2K-14	405.0	410.0	0.008	169947	
BC2K-14	410.0	412.5	0.002	169948	
BC2K-14	412.5	413.8	0.125	169949	
BC2K-14	413.8	420.0	0.020	169950	
BC2K-14	420.0	424.3	0.009	169951	
BC2K-14	424.3	425.0	0.111	169952	
BC2K-14	425.0	426.4	0.133	169953	
BC2K-14	426.4	430.0	0.001	169954	
BC2K-14	430.0	432.2	0.016	169955	
BC2K-14	432.2	433.7	0.070	169956	
BC2K-14	433.7	437.5	0.007	169957	
BC2K-14	437.5	440.2	0.009	169958	
BC2K-14	440.2	443.0	0.014	169959	
BC2K-14	443.0	445.8	0.018	169960	
BC2K-14	445.8	448.2	0.003	169961	
BC2K-14	448.2	455.0	0.001	169962	
BC2K-14	455.0	456.5	0.004	169963	
BC2K-14	456.5	461.0	0.003	169964	
BC2K-14	461.0	465.5	0.003	169965	
BC2K-15	183.3	190.0	0.002	169966	A001465
BC2K-15	190.0	195.0	0.023	169967	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-15	195.0	200.0	0.004	169968	
BC2K-15	200.0	205.0	0.908	169969	
BC2K-15	205.0	210.0	0.043	169970	
BC2K-15	210.0	215.0	0.148	169971	
BC2K-15	215.0	220.0	0.014	169972	
BC2K-15	220.0	225.0	0.003	169973	
BC2K-15	225.0	230.0	0.002	169974	
BC2K-15	230.0	234.6	0.001	169975	
BC2K-15	234.6	240.0	0.006	169976	
BC2K-15	240.0	245.0	0.002	169977	
BC2K-15	245.0	248.0	0.002	169978	
BC2K-15	248.0	253.5	0.018	169979	
BC2K-15	253.5	259.0	0.010	169980	
BC2K-15	259.0	265.0	0.032	169981	
BC2K-15	265.0	270.0	0.012	169982	
BC2K-15	270.0	275.0	0.001	169983	
BC2K-15	275.0	280.0	0.001	169984	
BC2K-15	280.0	285.0	0.001	169985	
BC2K-15	285.0	290.0	0.008	169986	
BC2K-15	290.0	295.0	0.023	169987	
BC2K-15	295.0	300.0	0.023	169988	
BC2K-15	300.0	303.1	0.012	169989	
BC2K-15	303.1	307.0	0.001	169990	
BC2K-15	345.0	350.0	0.001	169991	
BC2K-15	350.0	355.0	0.000	169992	
BC2K-15	365.0	370.0	0.000	169993	
BC2K-15	375.0	380.0	0.001	169994	
BC2K-15	380.0	385.0	0.031	169995	
BC2K-15	385.0	390.0	0.001	169996	
BC2K-15	410.0	415.0	0.000	169997	
BC2K-15	415.0	420.0	0.000	169998	
BC2K-15	420.0	425.0	0.000	169999	
BC2K-15	425.0	430.0	0.000	170000	
BC2K-15	430.0	435.0	0.000	172028	
BC2K-15	435.0	440.0	0.000	172029	
BC2K-15	440.0	445.0	0.000	172030	
BC2K-15	445.0	450.0	0.000	172031	
BC2K-15	455.0	460.0	0.000	172032	
BC2K-15	460.0	465.0	0.000	172033	
BC2K-16	85.0	90.0	0.000	172001	A001361
BC2K-16	90.0	95.0	0.000	172002	
BC2K-16	95.0	100.0	0.000	172003	
BC2K-16	100.0	105.0	0.000	172004	
BC2K-16	105.0	110.0	0.000	172005	
BC2K-16	110.0	115.0	0.000	172006	
BC2K-16	147.0	150.0	0.000	172007	
BC2K-16	150.0	155.0	0.000	172008	
BC2K-16	155.0	160.0	0.000	172009	
BC2K-16	160.0	165.0	0.001	172010	
BC2K-16	170.0	175.0	0.001	172011	
BC2K-16	189.5	193.0	0.000	172012	
BC2K-16	205.3	210.0	0.000	172013	
BC2K-16	210.0	215.0	0.000	172014	
BC2K-16	215.0	220.0	0.000	172015	
BC2K-16	225.0	230.0	0.000	172016	
BC2K-16	235.0	240.0	0.000	172017	
BC2K-16	240.0	245.0	0.000	172018	
BC2K-16	270.0	275.0	0.002	172019	
BC2K-16	282.5	285.0	0.010	172020	
BC2K-16	285.0	290.0	0.002	172021	
BC2K-16	290.0	295.0	0.006	172022	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-16	295.0	300.0	0.008	172023	
BC2K-16	300.0	305.0	0.007	172024	
BC2K-16	437.0	440.0	0.001	172025	
BC2K-16	440.0	443.5	0.413	172026	
BC2K-16	443.5	445.5	0.004	172027	
BC2K-17	30.0	40.0	0.002	0001	A001656
BC2K-17	40.0	45.0	0.001	0002	A001846
BC2K-17	45.0	50.0	0.003	0003	
BC2K-17	50.0	55.0	0.018	0004	
BC2K-17	55.0	60.0	0.003	0005	
BC2K-17	60.0	65.0	0.003	0006	
BC2K-17	65.0	70.0	0.000	0007	
BC2K-17	70.0	75.0	0.000	0008	
BC2K-17	75.0	80.0	0.000	0009	
BC2K-17	80.0	85.0	0.000	0010	
BC2K-17	85.0	90.0	0.004	0011	
BC2K-17	90.0	95.0	0.001	0012	
BC2K-17	95.0	100.0	0.001	172034	
BC2K-17	100.0	105.0	0.002	172035	
BC2K-17	105.0	110.0	0.003	0013	
BC2K-17	110.0	115.0	0.004	0014	
BC2K-17	115.0	120.0	0.007	0015	
BC2K-17	120.0	125.0	0.001	0016	
BC2K-17	125.0	130.0	0.001	0017	
BC2K-17	130.0	135.0	0.000	0018	
BC2K-17	135.0	140.0	0.001	172036	
BC2K-17	140.0	145.0	0.000	0019	
BC2K-17	145.0	150.0	0.000	0020	
BC2K-17	150.0	155.0	0.000	0021	
BC2K-17	155.0	160.0	0.000	0022	
BC2K-17	160.0	165.0	0.000	0023	
BC2K-17	165.0	170.0	0.000	0024	
BC2K-17	170.0	175.0	0.000	0025	
BC2K-17	175.0	180.0	0.001	0026	
BC2K-17	180.0	185.0	0.004	0027	
BC2K-17	185.0	190.0	0.000	0028	
BC2K-17	190.0	195.0	0.000	0029	
BC2K-17	194.0	198.0	0.000	17037	
BC2K-17	198.0	205.0	0.000	0030	
BC2K-17	205.0	210.0	0.000	0031	
BC2K-17	210.0	215.0	0.001	0032	
BC2K-17	215.0	220.0	0.000	0033	
BC2K-17	220.0	225.0	0.000	0034	
BC2K-17	225.0	228.6	0.000	0035	
BC2K-17	228.6	235.0	0.000	0036	
BC2K-17	235.0	240.0	0.000	0037	
BC2K-17	240.0	245.0	0.000	0038	
BC2K-17	245.0	250.0	0.000	0039	
BC2K-17	250.0	255.0	0.000	172038	
BC2K-17	255.0	260.0	0.000	0040	
BC2K-17	260.0	265.0	0.000	0041	
BC2K-17	265.0	270.0	0.000	0042	
BC2K-17	270.0	275.0	0.000	0043	
BC2K-17	275.0	280.0	0.000	0044	
BC2K-17	280.0	285.0	0.000	0045	
BC2K-17	285.0	290.0	0.000	172039	
BC2K-17	290.0	295.0	0.000	172040	
BC2K-17	295.0	300.0	0.000	0046	
BC2K-17	300.0	305.0	0.000	0047	
BC2K-17	305.0	310.0	0.000	0048	
BC2K-17	310.0	315.0	0.000	0049	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-17	315.0	320.0	0.000	172041	
BC2K-17	320.0	325.0	0.000	172042	
BC2K-17	325.0	330.0	0.000	0050	
BC2K-17	330.0	335.0	0.000	0051	
BC2K-17	335.0	340.0	0.000	0052	
BC2K-17	340.0	345.0	0.000	0053	
BC2K-17	345.0	350.0	0.000	0054	
BC2K-17	350.0	355.0	0.000	0055	
BC2K-17	355.0	360.0	0.000	172043	
BC2K-17	360.0	365.0	0.000	172044	
BC2K-17	365.0	370.0	0.000	0056	
BC2K-17	370.0	375.0	0.000	0057	
BC2K-17	375.0	380.0	0.000	0058	
BC2K-17	380.0	385.0	0.000	0059	
BC2K-17	385.0	390.0	0.000	172045	
BC2K-17	390.0	395.0	0.000	0060	
BC2K-17	395.0	400.0	0.000	0061	
BC2K-17	400.0	405.0	0.000	172046	
BC2K-17	405.0	410.0	0.000	0062	
BC2K-17	410.0	415.0	0.000	0063	
BC2K-17	415.0	420.0	0.000	0064	
BC2K-17	420.0	425.0	0.000	0065	
BC2K-17	425.0	430.0	0.000	0066	
BC2K-17	430.0	435.0	0.000	0067	
BC2K-17	435.0	440.0	0.000	0068	
BC2K-17	440.0	445.0	0.000	0069	
BC2K-17	445.0	450.0	0.000	0070	
BC2K-17	450.0	455.0	0.000	0071	
BC2K-17	455.0	460.0	0.000	0072	
BC2K-17	460.0	465.0	0.000	0073	
BC2K-17	465.0	470.0	0.000	172047	
BC2K-17	470.0	475.0	0.000	0074	
BC2K-17	475.0	480.0	0.000	0075	
BC2K-17	480.0	485.0	0.000	0076	
BC2K-17	490.0	495.0	0.000	172048	
BC2K-17	495.0	500.0	0.000	0077	
BC2K-17	500.0	505.0	0.000	0078	
BC2K-17	505.0	510.0	0.000	0079	
BC2K-17	510.0	515.0	0.000	0080	
BC2K-17	515.0	520.0	0.000	172049	
BC2K-17	520.0	525.0	0.000	172050	
BC2K-17	525.0	530.0	0.000	0081	
BC2K-17	530.0	535.0	0.000	0082	
BC2K-17	535.0	540.0	0.000	0083	
BC2K-17	540.0	545.0	0.000	172051	
BC2K-17	545.0	550.0	0.000	0084	
BC2K-17	550.0	555.0	0.000	0085	
BC2K-17	555.0	560.0	0.000	0086	
BC2K-17	560.0	565.0	0.000	0087	
BC2K-17	565.0	575.0	0.000	0088	
BC2K-18	54.0	60.0	0.000	0089	A001626
BC2K-18	60.0	65.0	0.000	0090	A001602
BC2K-18	65.0	70.0	0.025	0091	
BC2K-18	70.0	75.0	0.000	0092	
BC2K-18	75.0	80.0	0.002	0093	
BC2K-18	80.0	85.0	0.001	0094	
BC2K-18	85.0	90.0	0.001	0095	
BC2K-18	90.0	95.0	0.001	0096	
BC2K-18	95.0	100.0	0.015	0097	
BC2K-18	100.0	105.0	0.000	0098	
BC2K-18	105.0	110.0	0.018	0099	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-18	110.0	114.3	0.026	0100	
BC2K-18	114.3	120.6	0.024	0101	
BC2K-18	120.6	125.0	0.023	0102	
BC2K-18	125.0	130.0	0.007	0103	
BC2K-18	130.0	135.0	0.001	0104	
BC2K-18	135.0	140.0	0.022	0105	
BC2K-18	140.0	145.0	0.000	0106	
BC2K-18	195.0	200.0	0.004	0107	
BC2K-18	200.0	205.0	0.050	0108	
BC2K-18	205.0	210.0	0.002	0109	
BC2K-18	210.0	215.0	0.006	0111	
BC2K-18	215.0	220.0	0.001	0112	
BC2K-18	220.0	225.0	0.002	0113	
BC2K-18	225.0	230.0	0.000	0114	
BC2K-18	230.0	235.0	0.000	0115	
BC2K-18	235.0	240.0	0.000	0116	
BC2K-18	240.0	245.0	0.000	0117	
BC2K-18	245.0	250.0	0.000	0118	
BC2K-18	250.0	255.0	0.001	0119	
BC2K-18	255.0	258.5	0.001	0120	
BC2K-18	258.5	265.0	0.001	0121	
BC2K-18	265.0	270.0	0.001	0122	
BC2K-18	270.0	275.0	0.001	0123	
BC2K-18	275.0	280.0	0.000	0214	
BC2K-18	280.0	285.0	0.000	0215	
BC2K-18	285.0	290.0	0.001	0216	
BC2K-18	290.0	295.0	0.002	0217	
BC2K-18	295.0	300.0	0.001	0218	
BC2K-18	300.0	305.0	0.001	0219	
BC2K-18	305.0	311.9	0.001	0220	
BC2K-18	311.9	319.5	0.001	0221	
BC2K-18	319.5	325.0	0.001	0124	
BC2K-18	325.0	330.0	0.004	0125	
BC2K-18	330.0	335.0	0.002	0126	
BC2K-18	335.0	340.0	0.000	0127	
BC2K-18	340.0	345.0	0.001	0128	
BC2K-18	345.0	350.0	0.007	0129	
BC2K-18	350.0	355.0	0.001	0130	
BC2K-18	355.0	360.0	0.002	0132	
BC2K-18	360.0	365.0	0.001	0133	
BC2K-18	365.0	370.0	0.003	0134	
BC2K-18	370.0	375.0	0.002	0135	
BC2K-18	375.0	380.0	0.002	0136	
BC2K-18	380.0	385.0	0.001	0137	
BC2K-18	385.0	390.0	0.009	0138	
BC2K-18	390.0	395.0	0.001	0139	
BC2K-18	395.0	400.0	0.004	0140	
BC2K-18	400.0	405.0	0.000	0141	
BC2K-18	405.0	410.0	0.000	0142	
BC2K-18	410.0	415.0	0.002	0143	
BC2K-18	415.0	420.0	0.000	0144	
BC2K-18	420.0	425.0	0.001	0145	
BC2K-18	425.0	430.0	0.032	0146	
BC2K-18	430.0	435.0	0.001	0147	
BC2K-18	435.0	440.0	0.003	0148	
BC2K-18	440.0	445.0	0.000	0149	
BC2K-18	445.0	450.0	0.000	0150	
BC2K-18	450.0	455.0	0.000	0151	
BC2K-18	455.0	460.0	0.008	0153	
BC2K-18	460.0	465.1	0.000	0154	
BC2K-18	465.1	470.0	0.000	0155	
BC2K-18	470.0	475.0	0.000	0156	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-18	475.0	480.0	0.001	0157	
BC2K-18	480.0	485.0	0.001	0158	
BC2K-18	485.0	490.0	0.001	0159	
BC2K-18	490.0	495.0	0.001	0160	
BC2K-18	495.0	500.0	0.001	0161	
BC2K-18	500.0	505.0	0.000	0162	
BC2K-18	505.0	510.0	0.000	0163	
BC2K-18	510.0	515.0	0.001	0164	
BC2K-18	515.0	520.0	0.000	0165	
BC2K-18	520.0	525.0	0.000	0166	
BC2K-18	525.0	530.0	0.001	0167	
BC2K-18	530.0	535.0	0.003	0168	
BC2K-18	535.0	540.0	0.000	0169	
BC2K-18	540.0	545.0	0.000	0170	
BC2K-18	545.0	550.0	0.001	0171	
BC2K-18	550.0	555.0	0.008	0172	
BC2K-18	555.0	560.0	0.005	0173	
BC2K-18	560.0	565.0	0.002	0175	
BC2K-18	565.0	570.0	0.043	0176	
BC2K-18	570.0	575.0	0.001	0177	
BC2K-18	575.0	580.0	0.001	0178	
BC2K-18	580.0	585.0	0.000	0179	
BC2K-18	585.0	590.0	0.001	0180	
BC2K-18	590.0	595.0	0.000	0181	
BC2K-18	595.0	600.0	0.000	0182	
BC2K-18	600.0	605.0	0.000	0183	
BC2K-18	605.0	610.0	0.000	0184	
BC2K-18	610.0	615.0	0.000	0185	
BC2K-18	615.0	620.0	0.000	0186	
BC2K-18	620.0	625.0	0.000	0187	
BC2K-18	625.0	630.0	0.001	0188	
BC2K-18	630.0	635.0	0.001	0189	
BC2K-18	635.0	640.0	0.001	0190	
BC2K-18	640.0	645.0	0.000	0191	
BC2K-18	645.0	650.0	0.000	0192	
BC2K-18	650.0	655.0	0.001	0193	
BC2K-18	655.0	660.0	0.000	0194	
BC2K-18	660.0	665.0	0.001	0195	
BC2K-18	665.0	670.0	0.000	0197	
BC2K-18	670.0	675.0	0.000	0198	
BC2K-18	675.0	680.0	0.000	0199	
BC2K-18	680.0	685.0	0.000	0200	
BC2K-18	685.0	690.0	0.000	0201	
BC2K-18	690.0	698.6	0.001	0202	
BC2K-18	698.6	705.0	0.000	0203	
BC2K-18	705.0	710.0	0.001	0204	
BC2K-18	710.0	716.0	0.001	0205	
BC2K-18	716.0	720.0	0.001	0206	
BC2K-18	720.0	725.0	0.000	0207	
BC2K-18	725.0	730.0	0.001	0208	
BC2K-18	730.0	737.2	0.004	0209	
BC2K-18	737.2	744.7	0.002	0210	
BC2K-18	744.7	750.0	0.000	0211	
BC2K-18	750.0	755.0	0.000	0212	
BC2K-18	755.0	760.0	0.000	0213	
BC2K-19	60.0	65.0	0.000	0270	A001761
BC2K-19	65.0	70.0	0.002	0271	A001871
BC2K-19	70.0	75.0	0.008	0272	
BC2K-19	75.0	80.0	0.000	0273	
BC2K-19	91.5	96.8	0.071	0274	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-19	96.8	101.3	0.048	0275	
BC2K-19	101.3	106.1	0.004	0276	
BC2K-19	106.1	110.0	0.004	0277	
BC2K-19	210.0	215.0	0.000	0266	
BC2K-19	215.0	220.0	0.000	0267	
BC2K-19	220.0	225.0	0.002	0268	
BC2K-19	225.0	230.0	0.030	0269	
BC2K-19	250.0	258.0	0.001	0222	
BC2K-19	258.0	261.8	0.001	0223	
BC2K-19	261.8	268.0	0.044	0224	
BC2K-19	268.0	274.9	1.201	0225	
BC2K-19	274.9	280.0	0.435	0226	
BC2K-19	280.0	285.0	0.363	0227	
BC2K-19	285.0	291.4	0.068	0228	
BC2K-19	291.4	296.1	0.561	0229	
BC2K-19	296.1	300.0	1.079	0230	
BC2K-19	300.0	308.8	0.452	0231	
BC2K-19	308.8	310.0	1.210	0232	
BC2K-19	310.0	315.0	0.878	0233	
BC2K-19	315.0	315.8	0.361	0234	
BC2K-19	315.8	321.0	0.089	0235	
BC2K-19	321.0	326.0	0.621	0236	
BC2K-19	326.0	332.8	0.151	0237	
BC2K-19	332.8	337.0	0.001	0238	
BC2K-19	337.0	340.0	0.001	0239	
BC2K-19	340.0	345.0	0.000	0240	
BC2K-19	345.0	351.7	0.001	0241	
BC2K-19	351.7	357.0	0.002	0242	
BC2K-19	357.0	362.5	0.001	0244	
BC2K-19	362.5	366.6	0.203	0245	
BC2K-19	366.6	369.3	0.001	0246	
BC2K-19	369.3	374.0	0.039	0247	
BC2K-19	374.0	380.2	0.025	0249	
BC2K-19	380.2	386.0	0.002	0250	
BC2K-19	386.0	391.7	0.001	0251	
BC2K-19	391.7	392.5	0.036	0252	
BC2K-19	392.5	400.0	0.012	0253	
BC2K-19	400.0	404.5	0.016	0254	
BC2K-19	404.5	410.0	0.001	0255	
BC2K-19	410.0	415.0	0.000	0256	
BC2K-19	415.0	420.0	0.001	0257	
BC2K-19	420.0	424.6	0.001	0258	
BC2K-19	424.6	430.0	0.000	0259	
BC2K-19	430.0	435.7	0.000	0260	
BC2K-19	435.7	440.0	0.000	0261	
BC2K-19	440.0	443.5	0.000	0262	
BC2K-19	443.5	450.0	0.001	0263	
BC2K-19	450.0	455.0	0.000	0264	
BC2K-19	455.0	460.0	0.000	0265	
BC2K-20	80.0	85.0	0.016	0278	A001871
BC2K-20	85.0	90.0	0.017	0279	
BC2K-20	90.0	95.0	0.009	0280	
BC2K-20	95.0	100.0	0.008	0281	
BC2K-20	100.0	105.0	0.015	0282	
BC2K-20	216.0	221.0	0.003	0283	
BC2K-20	221.0	225.0	0.057	0284	
BC2K-20	225.0	230.0	0.002	0285	
BC2K-20	230.0	235.0	0.001	0286	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-20	235.0	240.0	0.003	0287	
BC2K-20	240.0	245.0	0.031	0288	
BC2K-20	245.0	250.0	0.043	0289	
BC2K-20	250.0	255.0	0.020	0290	
BC2K-20	255.0	260.0	0.008	0291	
BC2K-20	260.0	265.0	0.101	0292	
BC2K-20	265.0	270.0	0.037	0293	
BC2K-20	270.0	274.5	0.003	0294	
BC2K-20	274.5	278.0	0.123	0295	
BC2K-20	278.0	283.0	0.002	0296	
BC2K-20	283.0	289.0	0.011	0297	
BC2K-20	289.0	292.0	0.233	0298	
BC2K-20	369.0	374.5	0.000	0299	
BC2K-20	374.5	380.0	0.001	0300	
BC2K-20	380.0	385.0	0.000	0301	
BC2K-20	385.0	390.0	0.000	0302	
BC2K-20	393.5	394.1	0.000	0303	
BC2K-20	423.0	428.0	0.000	0304	
BC2K-20	428.0	432.0	0.000	0305	
BC2K-20	432.0	437.0	0.000	0306	
BC2K-20	437.0	442.5	0.000	0307	
BC2K-20	442.5	447.5	0.002	0308	
BC2K-21	30.0	40.0	0.008	0309	A001978
BC2K-21	40.0	45.0	0.004	0310	
BC2K-21	45.0	50.0	0.005	0311	
BC2K-21	50.0	55.0	0.006	0312	
BC2K-21	55.0	60.0	0.016	0313	
BC2K-21	60.0	65.0	0.016	0314	
BC2K-21	65.0	70.0	0.003	0315	
BC2K-21	70.0	75.0	0.005	0316	
BC2K-21	75.0	80.0	0.012	0317	
BC2K-21	80.0	81.2	0.007	0318	
BC2K-21	140.0	145.0	0.003	0319	
BC2K-21	145.0	150.0	0.001	0320	
BC2K-21	158.0	161.6	0.001	0321	
BC2K-21	161.6	166.0	0.000	0322	
BC2K-21	166.0	170.0	0.000	0323	
BC2K-21	170.0	175.0	0.001	0324	
BC2K-21	175.0	180.0	0.001	0325	
BC2K-21	180.0	185.0	0.000	0326	
BC2K-21	185.0	190.0	0.001	0327	
BC2K-21	190.0	195.0	0.001	0328	
BC2K-21	195.0	195.0	0.000	0330	
BC2K-21	200.0	205.0	0.000	0331	
BC2K-21	205.0	210.0	0.000	0332	
BC2K-21	210.0	215.0	0.000	0334	
BC2K-21	215.0	220.0	0.000	0335	
BC2K-21	220.0	225.0	0.000	0336	
BC2K-21	225.0	230.0	0.000	0337	
BC2K-21	230.0	235.0	0.000	0338	
BC2K-21	235.0	240.0	0.001	0339	
BC2K-21	249.2	253.4	0.001	0340	
BC2K-21	253.4	256.4	0.036	0341	
BC2K-22	36.5	38.3	0.028	0351	A001913

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-22	38.3	45.0	0.002	0352	
BC2K-22	45.0	50.0	0.003	0353	
BC2K-22	50.0	52.4	0.008	0354	
BC2K-22	52.4	60.0	0.045	0355	
BC2K-22	60.0	65.0	0.031	0356	
BC2K-22	65.0	70.0	0.034	0357	
BC2K-22	70.0	80.0	0.029	0358	
BC2K-22	80.0	86.5	0.008	0359	
BC2K-22	86.5	90.0	0.003	0360	
BC2K-22	118.0	123.0	0.001	0361	
BC2K-22	123.0	129.0	0.001	0362	
BC2K-22	129.0	134.0	0.001	0363	
BC2K-22	174.5	180.0	0.001	0364	
BC2K-22	180.0	185.0	0.001	0365	
BC2K-22	185.0	190.0	0.000	0366	
BC2K-22	190.0	195.0	0.000	0367	
BC2K-22	195.0	200.0	0.000	0368	
BC2K-22	200.0	205.0	0.002	0369	
BC2K-22	205.0	220.0	0.004	0370	
BC2K-22	220.0	225.0	0.000	0371	
BC2K-22	225.0	230.0	0.000	0374	
BC2K-22	230.0	235.0	0.000	0375	
BC2K-22	235.0	240.0	0.000	0376	
BC2K-22	240.0	245.0	0.000	0377	
BC2K-22	245.0	250.0	0.000	0378	
BC2K-22	250.0	255.0	0.000	0379	
BC2K-22	255.0	260.0	0.000	0380	
BC2K-22	260.0	265.0	0.000	0381	
BC2K-22	265.0	270.0	0.000	0382	
BC2K-22	270.0	275.0	0.000	0383	
BC2K-22	275.0	280.0	0.000	0384	
BC2K-22	280.0	285.0	0.000	0385	
BC2K-22	285.0	355.0	0.000	0386	
BC2K-22	355.0	360.0	0.000	0387	
BC2K-22	360.0	365.0	0.000	0388	
BC2K-22	365.0	370.0	0.000	0389	
BC2K-22	370.0	375.0	0.000	0390	
BC2K-23	57.0	65.0	0.000	0493	A002493
BC2K-23	65.0	75.0	0.000	0494	
BC2K-23	75.0	85.0	0.000	0495	
BC2K-23	85.0	95.0	0.000	0496	
BC2K-23	95.0	115.0	0.000	0497	
BC2K-23	115.0	120.0	0.000	0498	
BC2K-23	120.0	125.0	0.000	0499	
BC2K-23	125.0	135.0	0.000	0500	
BC2K-23	135.0	146.2	0.000	0613	
BC2K-23	146.2	155.0	0.000	0614	
BC2K-24	29.0	32.0	0.064	0391	A002215
BC2K-24	32.0	37.0	0.062	0392	
BC2K-24	37.0	44.0	0.077	0393	
BC2K-24	44.0	49.5	0.003	0394	
BC2K-24	49.5	57.0	0.259	0395	
BC2K-24	57.0	63.6	0.007	0396	
BC2K-24	63.6	67.0	0.001	0397	
BC2K-24	67.0	72.0	0.000	0398	
BC2K-24	72.0	77.0	0.000	0399	
BC2K-24	77.0	82.0	0.002	0400	
BC2K-24	82.0	87.0	0.004	0401	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-24	87.0	92.0	0.001	0402	
BC2K-24	92.0	97.5	0.001	0403	
BC2K-24	97.5	104.0	0.001	0404	
BC2K-24	104.0	109.0	0.001	0405	
BC2K-24	109.0	113.0	0.001	0406	
BC2K-24	117.0	122.0	0.001	0408	
BC2K-24	122.0	128.0	0.001	0409	
BC2K-24	128.0	132.0	0.001	0410	
BC2K-24	132.0	137.0	0.000	0411	
BC2K-24	137.0	142.0	0.008	0412	
BC2K-24	142.0	146.0	0.116	0413	
BC2K-24	146.0	151.0	0.043	0414	
BC2K-24	151.0	155.0	0.092	0415	
BC2K-24	155.0	160.3	0.027	0416	
BC2K-24	160.3	166.8	0.009	0417	
BC2K-24	166.8	172.0	0.016	0418	
BC2K-24	172.0	178.0	0.040	0419	
BC2K-24	178.0	182.0	0.041	0420	
BC2K-24	182.0	186.5	0.052	0421	
BC2K-24	186.5	191.0	0.006	0422	
BC2K-24	191.0	197.0	0.203	0423	
BC2K-24	197.0	202.0	0.027	0424	
BC2K-24	202.0	207.0	0.002	0425	
BC2K-24	207.0	212.0	0.003	0426	
BC2K-24	212.0	217.0	0.005	0427	
BC2K-24	217.0	222.0	0.002	0428	
BC2K-24	222.0	227.0	0.001	0429	
BC2K-24	227.0	232.0	0.001	0430	
BC2K-24	232.0	237.0	0.058	0431	
BC2K-24	237.0	242.0	0.034	0432	
BC2K-24	242.0	247.0	0.001	0433	
BC2K-24	247.0	252.0	0.001	0434	
BC2K-24	252.0	256.0	0.000	0435	
BC2K-24	256.0	261.0	0.000	0436	
BC2K-24	261.0	266.0	0.000	0437	
BC2K-24	266.0	268.0	0.000	0438	
BC2K-24	268.0	270.0	0.000	0439	
BC2K-24	270.0	276.0	0.000	0440	
BC2K-24	276.0	282.0	0.000	0441	
BC2K-24	282.0	285.0	0.008	0442	
BC2K-24	285.0	289.5	0.000	0443	
BC2K-24	289.5	297.0	0.000	0444	
BC2K-25	41.0	50.0	0.000	0501	A002493
BC2K-25	50.0	55.0	0.000	0502	
BC2K-25	55.0	60.0	0.000	0503	
BC2K-25	60.0	65.0	0.000	0504	
BC2K-25	65.0	70.0	0.000	0505	
BC2K-25	70.0	75.0	0.000	0506	
BC2K-25	75.0	80.0	0.000	0507	
BC2K-25	80.0	85.5	0.000	0508	
BC2K-25	85.5	88.2	0.000	0509	
BC2K-25	88.2	94.0	0.000	0510	
BC2K-25	94.0	100.0	0.000	0615	
BC2K-25	100.0	105.0	0.000	0616	
BC2K-25	105.0	110.0	0.000	0617	
BC2K-25	110.0	115.0	0.000	0618	
BC2K-25	115.0	120.0	0.000	0619	
BC2K-25	190.0	195.0	0.000	0620	
BC2K-25	195.0	198.3	0.000	0621	
BC2K-25	198.3	206.8	0.000	0622	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-25	206.8	213.8	0.000	0623	
BC2K-25	213.8	220.0	0.000	0624	
BC2K-25	220.0	225.0	0.000	0625	
BC2K-25	225.0	230.0	0.000	0626	
BC2K-25	230.0	235.0	0.000	0627	
BC2K-25	235.0	240.0	0.000	0628	
BC2K-25	240.0	245.0	0.000	0629	
BC2K-25	245.0	250.0	0.000	0630	
BC2K-25	250.0	255.0	0.000	0631	
BC2K-25	255.0	260.0	0.000	0632	
BC2K-26	61.0	70.0	0.002	0452	A002438
BC2K-26	70.0	75.0	0.003	0453	
BC2K-26	75.0	78.5	0.012	0454	
BC2K-26	78.5	81.5	0.001	0455	
BC2K-26	81.5	85.0	0.061	0456	
BC2K-26	85.0	87.5	0.008	0457	
BC2K-26	87.5	92.5	0.005	0458	
BC2K-26	92.5	98.3	0.001	0459	
BC2K-26	98.3	101.1	0.000	0460	
BC2K-26	101.1	106.5	0.001	0461	
BC2K-26	106.5	111.0	0.004	0462	
BC2K-26	111.0	116.0	0.089	0463	
BC2K-26	116.0	120.0	0.044	0464	
BC2K-26	120.0	126.0	0.056	0465	
BC2K-26	126.0	128.0	0.134	0466	
BC2K-26	128.0	133.0	0.003	0467	
BC2K-26	152.0	157.0	0.011	0468	
BC2K-26	157.0	162.0	0.000	0469	
BC2K-26	162.0	167.0	0.001	0470	
BC2K-26	167.0	170.0	0.017	0471	
BC2K-26	170.0	175.0	0.001	0472	
BC2K-26	175.0	180.0	0.001	0473	
BC2K-26	180.0	185.0	0.001	0475	
BC2K-26	185.0	190.0	0.005	0477	
BC2K-26	190.0	195.0	0.012	0478	
BC2K-26	195.0	200.0	0.009	0479	
BC2K-26	200.0	205.0	0.004	0480	
BC2K-26	205.0	210.0	0.015	0481	
BC2K-26	210.0	215.0	0.010	0482	
BC2K-26	215.0	220.0	0.003	0483	
BC2K-26	220.0	224.5	0.005	0484	
BC2K-26	224.5	229.5	0.084	0485	
BC2K-26	229.5	235.0	0.004	0486	
BC2K-26	235.0	240.0	0.001	0487	
BC2K-26	240.0	245.0	0.001	0488	
BC2K-26	245.0	250.0	0.002	0489	
BC2K-26	250.0	255.5	0.003	0490	
BC2K-26	255.5	257.0	0.054	0491	
BC2K-26	257.0	261.3	0.002	0492	
BC2K-27	71.6	77.5	0.005	0511	A002641
BC2K-27	77.5	88.5	0.003	0512	
BC2K-27	88.5	94.0	0.012	0513	
BC2K-27	94.0	102.5	0.001	0514	
BC2K-27	102.5	107.0	0.002	0515	
BC2K-27	107.0	113.0	0.001	0516	
BC2K-27	113.0	118.0	0.004	0517	
BC2K-27	118.0	124.0	0.245	0518	
BC2K-27	124.0	130.0	0.234	0519	
BC2K-27	130.0	134.5	0.001	0520	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-27	134.5	140.0	0.003	0521	
BC2K-27	140.0	146.0	0.000	0522	
BC2K-27	146.0	150.0	0.179	0523	
BC2K-27	150.0	155.0	0.000	0524	
BC2K-27	155.0	160.0	0.001	0525	
BC2K-27	160.0	165.0	0.001	0526	
BC2K-27	165.0	170.0	0.000	0527	
BC2K-27	170.0	175.0	0.000	0528	
BC2K-27	175.0	180.0	0.000	0529	
BC2K-27	180.0	185.0	0.000	0530	
BC2K-27	185.0	190.0	0.000	0531	
BC2K-27	190.0	195.0	0.000	0533	
BC2K-27	195.0	200.0	0.000	0534	
BC2K-27	200.0	205.0	0.001	0535	
BC2K-27	205.0	210.0	0.000	0537	
BC2K-27	210.0	215.0	0.001	0538	
BC2K-27	215.0	220.0	0.002	0539	
BC2K-27	220.0	225.0	0.001	0540	
BC2K-27	225.0	230.0	0.000	0541	
BC2K-27	230.0	235.0	0.104	0542	
BC2K-27	235.0	240.0	0.136	0543	
BC2K-27	240.0	245.0	0.045	0544	
BC2K-27	245.0	250.0	0.062	0545	
BC2K-27	250.0	255.0	0.271	0546	
BC2K-27	255.0	260.0	0.053	0547	
BC2K-27	260.0	265.0	0.040	0548	
BC2K-27	265.0	270.0	0.018	0549	
BC2K-27	270.0	275.0	0.057	0550	
BC2K-27	275.0	280.0	0.002	0601	
BC2K-27	280.0	285.0	0.011	0602	
BC2K-27	285.0	290.0	0.002	0603	
BC2K-27	290.0	295.0	0.993	0604	
BC2K-27	295.0	300.0	0.097	0606	
BC2K-27	300.0	305.0	0.485	0607	
BC2K-27	305.0	310.0	0.157	0608	
BC2K-27	340.0	345.0	0.025	0609	
BC2K-27	345.0	350.0	0.191	0610	
BC2K-27	350.0	355.0	0.002	0611	
BC2K-27	355.0	360.0	0.001	0612	
BC2K-28	65.0	70.0	0.005	0551	A002724
BC2K-28	70.0	75.0	0.003	0552	
BC2K-28	75.0	80.0	0.014	0553	
BC2K-28	80.0	85.0	0.007	0554	
BC2K-28	85.0	90.0	0.001	0555	
BC2K-28	90.0	97.5	0.002	0556	
BC2K-28	97.5	102.5	0.412	0557	
BC2K-28	102.5	105.0	0.010	0558	
BC2K-28	107.5	110.0	0.002	0559	
BC2K-28	113.2	120.0	0.004	0560	
BC2K-28	120.0	125.0	0.009	0561	
BC2K-28	125.0	131.8	0.112	0562	
BC2K-28	131.8	138.0	0.002	0563	
BC2K-28	138.0	145.0	0.001	0564	
BC2K-28	145.0	150.0	0.001	0565	
BC2K-28	150.0	155.0	0.002	0566	
BC2K-28	225.2	230.0	0.000	0567	
BC2K-28	230.0	235.0	0.000	0568	
BC2K-28	235.0	240.0	0.000	0569	
BC2K-28	240.0	245.0	0.001	0570	
BC2K-28	245.0	250.0	0.004	0572	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-28	250.0	255.0	0.002	0573	
BC2K-28	255.0	260.0	0.016	0574	
BC2K-28	260.0	265.0	0.054	0576	
BC2K-28	265.0	270.0	0.220	0577	
BC2K-28	270.0	275.0	0.041	0578	
BC2K-28	275.0	280.0	0.006	0579	
BC2K-28	280.0	285.0	0.003	0580	
BC2K-28	285.0	290.0	0.009	0581	
BC2K-28	290.0	295.0	0.008	0582	
BC2K-28	295.0	300.0	0.001	0583	
BC2K-28	300.0	305.0	0.002	0584	
BC2K-28	305.0	310.0	0.009	0585	
BC2K-28	310.0	315.0	0.033	0586	
BC2K-28	315.0	320.0	0.032	0587	
BC2K-28	320.0	325.0	0.002	0588	
BC2K-28	395.0	400.0	0.000	0589	
BC2K-28	400.0	405.0	0.000	0590	
BC2K-28	405.0	410.0	0.000	0591	
BC2K-28	410.0	415.0	0.001	0592	
BC2K-29	70.0	78.6	0.001	0651	A002860
BC2K-29	78.6	85.0	0.038	0652	
BC2K-29	85.0	90.0	0.001	0653	
BC2K-29	90.0	94.8	0.002	0654	
BC2K-29	94.8	100.0	0.002	0655	
BC2K-29	100.0	105.3	0.016	0656	
BC2K-29	105.3	108.8	0.000	0657	
BC2K-29	108.8	115.0	0.001	0658	
BC2K-29	115.0	120.0	0.001	0659	
BC2K-29	120.0	125.0	0.001	0660	
BC2K-29	125.0	130.0	0.000	0661	
BC2K-29	130.0	135.0	0.001	0662	
BC2K-29	135.0	140.0	0.000	0663	
BC2K-29	140.0	145.0	0.000	0664	
BC2K-29	145.0	150.0	0.001	0665	
BC2K-29	150.0	154.5	0.001	0666	
BC2K-29	154.5	160.0	0.000	0667	
BC2K-29	160.0	165.0	0.001	0668	
BC2K-29	165.0	170.0	0.003	0669	
BC2K-29	170.0	174.8	0.000	0670	
BC2K-29	174.8	180.7	0.027	0674	
BC2K-29	180.7	183.4	0.585	0675	
BC2K-29	183.4	185.0	0.006	0676	
BC2K-29	185.0	188.7	0.001	0677	
BC2K-29	188.7	195.8	0.014	0678	
BC2K-29	195.8	200.0	0.608	0679	
BC2K-29	200.0	205.7	0.011	0680	
BC2K-29	205.7	213.1	0.006	0681	
BC2K-29	213.1	216.5	0.421	0682	
BC2K-29	216.5	220.0	0.006	0683	
BC2K-29	220.0	226.3	0.071	0684	
BC2K-29	226.3	230.0	0.695	0685	
BC2K-29	230.0	235.0	1.556	0686	
BC2K-29	235.0	240.0	1.234	0687	
BC2K-29	240.0	242.0	0.732	0688	
BC2K-29	242.0	246.5	1.512	0689	
BC2K-29	246.5	250.0	0.081	0690	
BC2K-29	250.0	252.1	0.144	0691	
BC2K-29	252.1	256.8	0.012	0692	
BC2K-29	256.8	260.0	0.012	0693	
BC2K-29	260.0	265.0	0.000	0697	
BC2K-29	265.0	270.0	0.001	0698	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-29	270.0	277.7	0.000	0699	
BC2K-29	277.7	280.0	0.002	0700	
BC2K-29	280.0	285.0	0.013	0701	
BC2K-29	285.0	290.0	0.001	0702	
BC2K-29	290.0	293.3	0.000	0703	
BC2K-29	293.3	297.5	0.001	0704	
BC2K-29	297.5	301.5	0.004	0705	
BC2K-29	301.5	305.0	0.001	0706	
BC2K-29	305.0	310.0	0.001	0707	
BC2K-29	310.0	315.7	0.000	0708	
BC2K-29	315.7	320.0	0.000	0709	
BC2K-29	320.0	325.2	0.000	0710	
BC2K-29	325.2	330.0	0.001	0711	
BC2K-29	330.0	336.7	0.001	0712	
BC2K-29	336.7	337.8	0.002	0713	
BC2K-29	337.8	340.0	0.000	0714	
BC2K-29	340.0	345.0	0.001	0715	
BC2K-29	345.0	351.2	0.001	0716	
BC2K-29	351.2	356.2	0.001	0720	
BC2K-29	356.2	360.0	0.002	0721	
BC2K-29	360.0	365.1	0.001	0722	
BC2K-29	365.1	370.6	0.000	0723	
BC2K-29	410.0	414.2	0.001	0724	
BC2K-29	414.2	418.4	0.000	0725	
BC2K-29	418.4	421.4	0.000	0726	
BC2K-29	421.4	425.4	0.001	0727	
BC2K-29	425.4	430.0	0.001	0728	
BC2K-30	116.3	120.0	0.000	0751	A003016
BC2K-30	120.0	127.5	0.000	0752	
BC2K-30	127.5	133.5	0.000	0753	
BC2K-30	133.5	140.5	0.004	0754	
BC2K-30	140.5	145.0	0.005	0755	
BC2K-30	145.0	150.0	0.004	0756	
BC2K-30	150.0	156.0	0.002	0757	
BC2K-30	156.0	160.0	0.003	0758	
BC2K-30	160.0	165.0	0.685	0759	
BC2K-30	165.0	169.5	0.380	0760	
BC2K-30	169.5	173.0	0.111	0761	
BC2K-30	173.0	180.0	0.035	0762	
BC2K-30	180.0	186.0	0.274	0763	
BC2K-30	186.0	192.0	0.051	0764	
BC2K-30	192.0	197.5	0.523	0765	
BC2K-30	197.5	202.0	0.128	0766	
BC2K-30	202.0	205.0	0.005	0767	
BC2K-30	205.0	211.0	0.006	0768	
BC2K-30	211.0	215.0	0.003	0769	
BC2K-30	215.0	220.0	0.002	0770	
BC2K-30	220.0	224.0	0.015	0772	
BC2K-30	224.0	230.0	0.003	0773	
BC2K-30	230.0	234.5	0.031	0774	
BC2K-30	234.5	240.0	0.005	0775	
BC2K-30	240.0	245.0	0.001	0776	
BC2K-30	245.0	250.0	0.000	0777	
BC2K-30	250.0	255.0	0.011	0778	
BC2K-30	255.0	260.0	0.039	0779	
BC2K-30	260.0	264.5	0.037	0780	
BC2K-30	264.5	269.0	0.059	0781	
BC2K-30	269.0	275.0	0.024	0782	
BC2K-30	275.0	280.0	0.076	0783	
BC2K-30	280.0	285.0	0.008	0784	
BC2K-30	285.0	290.0	0.020	0785	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-30	290.0	295.0	0.020	0786	
BC2K-30	295.0	300.0	0.064	0787	
BC2K-30	300.0	307.5	0.068	0788	
BC2K-30	307.5	310.0	0.205	0789	
BC2K-30	310.0	316.0	0.200	0790	
BC2K-30	316.0	320.0	0.078	0792	
BC2K-30	320.0	326.5	0.277	0793	
BC2K-30	326.5	334.5	0.043	0794	
BC2K-30	334.5	340.0	0.407	0795	
BC2K-30	340.0	342.0	0.812	0796	
BC2K-30	342.0	346.2	0.066	0797	
BC2K-30	346.2	350.0	0.114	0798	
BC2K-30	350.0	355.0	0.047	0799	
BC2K-30	355.0	357.5	0.006	0800	
BC2K-30	357.5	362.0	0.106	0801	
BC2K-30	362.0	370.0	0.010	0802	
BC2K-30	370.0	375.0	0.001	0803	
BC2K-30	375.0	380.0	0.001	0804	
BC2K-30	380.0	385.0	0.001	0805	
BC2K-30	385.0	390.0	0.005	0806	
BC2K-30	390.0	394.0	0.023	0807	
BC2K-30	394.0	399.0	0.006	0808	
BC2K-30	399.0	405.0	0.003	0809	
BC2K-30	405.0	410.0	0.001	0810	
BC2K-30	410.0	415.0	0.000	0812	
BC2K-30	415.0	420.0	0.000	0813	
BC2K-31	190.8	195.0	0.068	0816	A003184
BC2K-31	195.0	199.3	0.002	0817	
BC2K-31	199.3	205.0	0.068	0818	
BC2K-31	205.0	210.5	0.168	0819	
BC2K-31	210.5	215.4	0.485	0820	
BC2K-31	215.4	221.0	1.171	0821	
BC2K-31	221.0	225.9	0.596	0822	
BC2K-31	225.9	230.0	0.292	0823	
BC2K-31	230.0	235.0	0.200	0824	
BC2K-31	235.0	240.0	0.067	0825	
BC2K-31	240.0	245.0	0.165	0826	
BC2K-31	245.0	250.0	0.070	0827	
BC2K-31	250.0	255.0	0.674	0828	
BC2K-31	255.0	260.0	0.007	0829	
BC2K-31	260.0	265.0	0.186	0830	
BC2K-31	265.0	270.0	0.305	0831	
BC2K-31	270.0	275.0	0.075	0832	
BC2K-31	275.0	280.0	0.031	0833	
BC2K-31	280.0	286.0	0.002	0834	
BC2K-31	286.0	293.0	0.002	0835	
BC2K-31	293.0	301.0	0.001	0836	
BC2K-31	301.0	306.0	0.000	0837	
BC2K-31	306.0	311.0	0.000	0841	
BC2K-31	311.0	315.0	0.000	0842	
BC2K-31	315.0	320.0	0.001	0843	
BC2K-31	320.0	325.0	0.013	0844	
BC2K-31	325.0	330.0	0.006	0845	
BC2K-31	330.0	335.0	0.083	0846	
BC2K-31	335.0	340.0	0.027	0847	
BC2K-31	340.0	345.0	0.089	0848	
BC2K-31	345.0	350.0	0.002	0849	
BC2K-31	350.0	355.0	0.002	0850	
BC2K-31	355.0	360.0	0.001	0901	
BC2K-31	420.0	425.0	0.001	0902	
BC2K-31	425.0	430.0	0.000	0903	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-31	430.0	435.0	0.000	0904	
BC2K-31	435.0	440.0	0.000	0905	
BC2K-31	440.0	445.3	0.000	0906	
BC2K-32	86.5	91.0	0.010	0851	A003051
BC2K-32	91.0	101.8	0.002	0852	
BC2K-32	101.8	107.2	0.001	0853	
BC2K-32	107.2	113.7	0.002	0854	
BC2K-32	113.7	117.1	0.017	0855	
BC2K-32	117.1	122.0	0.115	0856	
BC2K-32	122.0	127.0	0.018	0857	
BC2K-32	127.0	130.0	0.237	0858	
BC2K-32	130.0	135.0	0.093	0859	
BC2K-32	135.0	140.0	0.067	0860	
BC2K-32	140.0	145.0	0.024	0861	
BC2K-32	145.0	149.0	0.036	0862	
BC2K-32	149.0	152.7	0.004	0863	
BC2K-32	152.7	156.0	0.009	0864	
BC2K-32	156.0	161.0	0.002	0865	
BC2K-32	161.0	165.6	0.001	0866	
BC2K-32	165.6	170.0	0.000	0867	
BC2K-32	170.0	175.0	0.008	0868	
BC2K-32	175.0	180.0	0.000	0869	
BC2K-32	180.0	185.0	0.001	0870	
BC2K-32	185.0	190.0	0.002	0873	
BC2K-32	190.0	193.5	0.000	0874	
BC2K-32	193.5	197.0	0.002	0875	
BC2K-32	197.0	200.0	0.147	0876	
BC2K-32	200.0	204.0	0.596	0877	
BC2K-32	204.0	208.5	0.254	0878	
BC2K-32	208.5	212.8	0.120	0879	
BC2K-32	212.8	218.0	0.117	0880	
BC2K-32	218.0	223.0	0.217	0882	
BC2K-32	223.0	228.0	0.158	0883	
BC2K-32	228.0	234.0	0.237	0884	
BC2K-32	234.0	240.0	1.716	0885	
BC2K-32	240.0	245.0	0.473	0886	
BC2K-32	245.0	250.0	0.267	0887	
BC2K-32	250.0	255.0	0.169	0888	
BC2K-32	255.0	260.5	0.952	0889	
BC2K-32	260.5	265.0	0.167	0890	
BC2K-32	265.0	270.0	0.304	0891	
BC2K-32	270.0	275.0	0.396	0892	
BC2K-32	275.0	280.0	0.328	0893	
BC2K-32	280.0	285.0	0.137	0894	
BC2K-32	285.0	290.0	0.095	0898	
BC2K-32	290.0	295.0	0.467	0899	
BC2K-32	295.0	300.0	0.001	0900	
BC2K-32	300.0	305.0	0.001	0729	
BC2K-32	305.0	310.0	0.112	0730	
BC2K-32	310.0	315.0	0.260	0731	
BC2K-32	315.0	320.0	0.002	0732	
BC2K-32	320.0	325.0	0.074	0733	
BC2K-32	325.0	330.0	0.190	0734	
BC2K-32	330.0	335.0	0.120	0735	
BC2K-32	335.0	340.0	0.677	0736	
BC2K-32	340.0	345.0	0.667	0737	
BC2K-32	345.0	350.0	0.003	0738	
BC2K-32	350.0	355.0	0.002	0739	
BC2K-32	355.0	360.0	0.001	0740	
BC2K-32	360.0	365.0	0.001	0741	
BC2K-32	365.0	370.0	0.000	0742	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-32	370.0	375.0	0.000	0743	
BC2K-32	375.0	380.0	0.000	0744	
BC2K-32	380.0	385.0	0.000	0745	
BC2K-32	385.0	390.0	0.000	0746	
BC2K-32	410.0	415.0	0.001	0747	
BC2K-33	70.5	72.5	0.159	0907	A003199 A003830
BC2K-33	200.0	205.0	0.002	0908	
BC2K-33	205.0	210.0	0.051	0909	
BC2K-33	210.0	215.0	0.019	0910	
BC2K-33	215.0	219.5	0.002	0911	
BC2K-33	219.5	223.7	0.009	0912	
BC2K-33	223.7	230.0	0.051	0913	
BC2K-33	230.0	235.0	0.150	0914	
BC2K-33	235.0	240.0	0.366	0915	
BC2K-33	240.0	245.0	0.372	0916	
BC2K-33	245.0	250.0	0.011	0917	
BC2K-33	250.0	255.0	0.023	0918	
BC2K-33	255.0	260.0	0.027	0919	
BC2K-33	260.0	265.0	0.001	0920	
BC2K-33	265.0	270.0	0.001	0921	
BC2K-33	380.0	385.0	0.000	1601	
BC2K-33	385.0	390.0	0.000	1602	
BC2K-33	390.0	395.0	0.001	1603	
BC2K-33	395.0	400.0	0.001	1604	
BC2K-33	400.0	405.0	0.000	1605	
BC2K-33	405.0	410.0	0.000	1606	
BC2K-33	410.0	415.0	0.000	1607	
BC2K-33	415.0	420.0	0.000	1608	
BC2K-33	420.0	425.0	0.000	1609	
BC2K-33	425.0	430.0	0.000	1610	
BC2K-33	430.0	435.0	0.000	1611	
BC2K-33	435.0	440.0	0.000	1612	
BC2K-33	440.0	445.0	0.000	1613	
BC2K-33	445.0	450.0	0.000	1614	
BC2K-33	450.0	455.0	0.000	1615	
BC2K-33	455.0	460.0	0.000	1616	
BC2K-33	460.0	465.0	0.000	1617	
BC2K-33	465.0	470.0	0.000	1618	
BC2K-33	506.0	510.0	0.000	0922	
BC2K-33	510.0	515.0	0.000	0923	
BC2K-33	515.0	520.0	0.000	0924	
BC2K-33	582.8	585.8	0.982	0927	
BC2K-33	585.8	590.0	0.123	0928	
BC2K-33	590.0	594.0	0.268	0929	
BC2K-33	594.0	596.3	0.409	0930	
BC2K-33	596.3	599.3	0.029	0931	
BC2K-34	66.0	75.0	0.001	0951	A003473
BC2K-34	75.0	80.0	0.001	0952	
BC2K-34	80.0	85.0	0.000	0953	
BC2K-34	85.0	90.0	0.000	0954	
BC2K-34	90.0	95.0	0.001	0955	
BC2K-34	95.0	98.0	0.000	0956	
BC2K-34	98.0	102.0	0.000	0957	
BC2K-34	102.0	107.0	0.000	0958	
BC2K-34	107.0	112.0	0.000	0959	
BC2K-34	112.0	117.0	0.000	0960	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-34	117.0	121.0	0.000	0961	
BC2K-34	121.0	125.0	0.000	0962	
BC2K-34	125.0	130.3	0.000	0963	
BC2K-34	130.3	135.0	0.000	0964	
BC2K-34	135.0	140.0	0.000	0965	
BC2K-34	140.0	150.0	0.000	0966	
BC2K-34	150.0	155.0	0.000	0967	
BC2K-34	155.0	160.0	0.000	0968	
BC2K-34	160.0	165.0	0.001	0969	
BC2K-34	165.0	170.0	0.000	0970	
BC2K-34	170.0	175.0	0.003	0971	
BC2K-34	175.0	180.0	0.000	0972	
BC2K-34	180.0	185.0	0.001	0973	
BC2K-34	185.0	190.0	0.000	0974	
BC2K-34	190.0	193.0	0.000	0975	
BC2K-34	193.0	198.0	0.000	0978	
BC2K-34	198.0	203.0	0.003	0979	
BC2K-34	203.0	207.0	0.004	0980	
BC2K-34	207.0	209.3	0.006	0981	
BC2K-34	209.3	215.0	0.004	0982	
BC2K-34	215.0	220.0	0.006	0983	
BC2K-35	60.0	71.3	0.001	0932	A003584
BC2K-35	71.3	76.3	0.001	0933	
BC2K-35	76.3	81.0	0.002	0934	
BC2K-35	81.0	86.0	0.000	0935	
BC2K-35	86.0	90.0	0.001	0936	
BC2K-35	90.0	95.0	0.000	0937	
BC2K-35	95.0	100.0	0.000	0938	
BC2K-35	100.0	105.0	0.000	0939	
BC2K-35	105.0	110.0	0.000	0940	
BC2K-35	110.0	115.0	0.000	0941	
BC2K-35	115.0	120.0	0.000	0942	
BC2K-35	120.0	125.0	0.000	0943	
BC2K-35	125.0	130.0	0.000	0944	
BC2K-35	130.0	133.8	0.000	0945	
BC2K-35	158.0	162.3	0.000	0946	
BC2K-35	162.3	167.0	0.000	0947	
BC2K-35	167.0	172.0	0.000	0948	
BC2K-35	167.0	172.0	0.000	0949	
BC2K-35	172.0	177.0	0.000	0950	
BC2K-35	177.0	182.0	0.000	0985	
BC2K-35	182.0	187.0	0.000	0986	
BC2K-35	187.0	192.0	0.000	0987	
BC2K-35	192.0	196.0	0.000	0988	
BC2K-35	196.0	200.0	0.000	0989	
BC2K-35	200.0	205.0	0.000	0990	
BC2K-35	205.0	210.0	0.000	0991	
BC2K-35	210.0	215.0	0.000	0992	
BC2K-35	215.0	226.0	0.000	0993	
BC2K-35	226.0	235.0	0.000	0994	
BC2K-35	235.0	240.2	0.001	0995	
BC2K-35	240.2	245.0	0.000	0996	
BC2K-35	245.0	250.0	0.001	0997	
BC2K-35	250.0	255.0	0.000	0998	
BC2K-35	255.0	260.0	0.000	0999	
BC2K-35	260.0	265.0	0.000	1000	
BC2K-35	265.0	270.0	0.001	1501	
BC2K-35	270.0	275.0	0.000	1502	
BC2K-35	275.0	280.0	0.000	1503	
BC2K-35	280.0	290.0	0.000	1504	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-36	70.2	78.0	0.001	1505	A003624
BC2K-36	78.0	83.5	0.002	1506	
BC2K-36	83.5	87.0	0.000	1507	
BC2K-36	87.0	90.8	0.000	1508	
BC2K-36	90.8	95.0	0.012	1509	
BC2K-36	95.0	100.0	0.000	1510	
BC2K-36	100.0	105.0	0.001	1511	
BC2K-36	105.0	110.0	0.007	1512	
BC2K-36	110.0	115.0	0.000	1513	
BC2K-36	115.0	120.0	0.008	1514	
BC2K-36	120.0	125.0	0.017	1515	
BC2K-36	125.0	130.0	0.014	1516	
BC2K-36	130.0	135.0	0.002	1517	
BC2K-36	135.0	140.0	0.001	1518	
BC2K-36	140.0	145.0	0.000	1519	
BC2K-36	145.0	150.0	0.000	1520	
BC2K-36	150.0	155.0	0.000	1521	
BC2K-36	163.3	166.3	0.000	1522	
BC2K-36	195.0	200.0	0.000	1523	
BC2K-36	200.0	205.0	0.000	1524	
BC2K-36	205.0	210.0	0.000	1526	
BC2K-36	210.0	215.0	0.000	1527	
BC2K-36	232.0	236.0	0.001	1528	
BC2K-36	236.0	240.0	0.001	1529	
BC2K-36	240.0	245.0	0.000	1530	
BC2K-36	245.0	250.0	0.000	1531	
BC2K-36	270.0	275.0	0.000	1532	
BC2K-36	275.0	280.0	0.000	1533	
BC2K-36	280.0	285.0	0.000	1534	
BC2K-36	285.0	290.0	0.000	1535	
BC2K-37	101.2	107.5	0.003	1536	A003727
BC2K-37	107.5	113.2	0.001	1537	
BC2K-37	113.2	117.3	0.001	1538	
BC2K-37	117.3	120.0	0.004	1539	
BC2K-37	120.0	125.0	0.001	1540	
BC2K-37	125.0	130.0	0.006	1541	
BC2K-37	130.0	135.0	0.002	1542	
BC2K-37	135.0	140.0	0.000	1543	
BC2K-37	140.0	145.0	0.019	1544	
BC2K-37	145.0	150.0	0.015	1545	
BC2K-37	150.0	155.0	0.000	1546	
BC2K-37	155.0	160.0	0.000	1547	
BC2K-37	160.0	165.0	0.000	1548	
BC2K-37	165.0	170.0	0.000	1549	
BC2K-37	170.0	175.0	0.001	1550	
BC2K-37	175.0	180.0	0.001	1551	
BC2K-37	180.0	185.0	0.001	1552	
BC2K-37	185.0	190.0	0.001	1553	
BC2K-37	190.0	194.0	0.001	1554	
BC2K-37	194.0	198.6	0.002	1555	
BC2K-37	198.6	201.5	0.000	1556	
BC2K-37	312.6	315.6	0.000	1557	
BC2K-37	315.6	320.0	0.000	1558	
BC2K-37	320.0	325.0	0.000	1559	
BC2K-37	325.0	330.0	0.000	1560	
BC2K-37	330.0	335.0	0.000	1561	
BC2K-37	335.0	339.0	0.001	1562	
BC2K-37	339.0	342.0	0.006	1563	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-37	339.0	342.0	0.004	1564	
BC2K-37	342.0	348.5	0.031	1565	
BC2K-37	348.5	350.8	0.034	1566	
BC2K-37	350.8	355.0	0.003	1567	
BC2K-37	355.0	360.0	0.012	1568	
BC2K-37	360.0	365.0	0.001	1569	
BC2K-38	100.0	105.0	0.012	1570	A004066
BC2K-38	105.0	110.0	0.025	1571	
BC2K-38	110.0	115.0	0.033	1572	
BC2K-38	115.0	120.0	0.005	1573	
BC2K-38	120.0	130.0	0.001	1574	
BC2K-38	130.0	135.0	0.000	1575	
BC2K-38	135.0	140.0	0.000	1576	
BC2K-38	140.0	146.0	0.000	1577	
BC2K-38	146.0	158.0	0.001	1578	
BC2K-38	188.0	193.0	0.000	1579	
BC2K-38	193.0	196.0	0.000	1580	
BC2K-38	196.0	201.0	0.000	1581	
BC2K-38	201.0	206.0	0.001	1582	
BC2K-38	206.0	210.0	0.000	1583	
BC2K-38	210.0	215.0	0.000	1584	
BC2K-38	215.0	220.0	0.001	1585	
BC2K-38	220.0	225.0	0.000	1586	
BC2K-38	225.0	230.0	0.000	1587	
BC2K-38	230.0	235.0	0.000	1588	
BC2K-38	235.0	240.0	0.000	1590	
BC2K-38	240.0	245.0	0.000	1591	
BC2K-38	245.0	250.0	0.001	1592	
BC2K-38	250.0	255.0	0.001	1593	
BC2K-38	255.0	260.0	0.014	1594	
BC2K-38	260.0	265.0	0.013	1595	
BC2K-38	265.0	270.0	0.060	1596	
BC2K-38	270.0	275.0	0.040	1597	
BC2K-38	275.0	280.0	0.002	1598	
BC2K-38	280.0	285.0	0.001	1599	
BC2K-38	285.0	289.5	0.033	1600	
BC2K-38	289.5	295.0	0.084	1651	
BC2K-38	295.0	300.0	0.153	1652	
BC2K-38	300.0	305.0	0.011	1653	
BC2K-38	305.0	309.4	0.001	1654	
BC2K-38	309.4	316.0	0.020	1655	
BC2K-38	316.0	322.0	0.001	1656	
BC2K-38	322.0	327.0	0.032	1657	
BC2K-38	327.0	331.0	0.013	1658	
BC2K-38	331.0	336.0	0.016	1659	
BC2K-38	336.0	340.5	0.003	1660	
BC2K-38	340.5	342.5	0.020	1661	
BC2K-38	342.5	347.5	0.005	1662	
BC2K-39	117.0	121.0	0.001	1619	A004103
BC2K-39	121.0	130.0	0.007	1620	
BC2K-39	130.0	135.0	0.004	1621	
BC2K-39	155.0	160.0	0.001	1622	
BC2K-39	160.0	165.0	0.001	1623	
BC2K-39	165.0	170.0	0.011	1624	
BC2K-39	170.0	175.0	0.000	1625	
BC2K-39	175.0	180.0	0.001	1626	
BC2K-39	266.0	271.0	0.000	1627	
BC2K-39	271.0	276.0	0.000	1628	
BC2K-39	276.0	280.0	0.000	1629	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-39	280.0	285.0	0.001	1630	
BC2K-39	280.0	285.0	0.000	1631	
BC2K-39	345.0	350.0	0.001	1634	
BC2K-39	350.0	355.0	0.000	1635	
BC2K-39	355.0	360.0	0.000	1636	
BC2K-39	360.0	365.0	0.000	1637	
BC2K-39	365.0	370.0	0.000	1638	
BC2K-39	370.0	376.0	0.001	1639	
BC2K-40	115.0	120.0	0.000	1665	A004151
BC2K-40	120.0	125.0	0.000	1666	
BC2K-40	125.0	130.0	0.000	1667	
BC2K-40	130.0	135.0	0.000	1668	
BC2K-40	135.0	140.0	0.000	1669	
BC2K-40	140.0	145.0	0.000	1670	
BC2K-40	145.0	150.0	0.001	1671	
BC2K-40	150.0	160.0	0.000	1672	
BC2K-40	160.0	165.4	0.000	1673	
BC2K-40	165.4	170.0	0.001	1674	
BC2K-40	170.0	175.0	0.000	1675	
BC2K-40	263.0	266.5	0.000	1676	
BC2K-40	266.4	270.0	0.000	1677	
BC2K-40	270.0	275.0	0.000	1678	
BC2K-40	275.0	280.0	0.001	1679	
BC2K-40	280.0	285.0	0.000	1680	
BC2K-40	285.0	290.0	0.001	1682	
BC2K-40	310.0	315.0	0.001	1685	
BC2K-40	315.0	320.0	0.002	1686	
BC2K-40	320.0	323.5	0.003	1687	
BC2K-41	175.0	180.0	0.000	1688	A004435
BC2K-41	180.0	185.0	0.000	1689	
BC2K-41	185.0	190.0	0.000	1690	
BC2K-41	200.0	205.0	0.000	1691	
BC2K-41	205.0	210.0	0.000	1692	
BC2K-41	310.0	315.0	0.000	1693	
BC2K-41	315.0	320.0	0.001	1694	
BC2K-41	343.8	346.5	0.004	1695	
BC2K-42	35.0	40.0	0.002	1788	A004754
BC2K-42	40.0	45.0	0.005	1789	
BC2K-42	133.0	134.7	0.083	1791	
BC2K-42	141.5	145.0	0.088	1792	
BC2K-42	145.0	153.6	0.019	1796	
BC2K-42	153.6	158.5	0.333	1797	
BC2K-42	158.5	165.8	0.030	1798	
BC2K-42	165.8	170.3	0.015	1799	
BC2K-42	170.3	180.0	0.004	1800	
BC2K-42	180.0	189.3	0.001	1801	
BC2K-42	333.5	334.6	0.001	1805	
BC2K-42	368.8	379.0	0.000	1806	
BC2K-42	379.0	383.5	0.000	1807	
BC2K-42	383.5	390.0	0.000	1808	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-42	390.0	400.0	0.000	1809	
BC2K-42	430.0	440.0	0.000	1812	
BC2K-42	440.0	446.5	0.020	1816	
BC2K-42	455.4	460.0	0.008	1817	
BC2K-42	460.0	465.0	0.007	1818	
BC2K-43	16.0	20.0	0.000	1701	A004451
BC2K-43	20.0	25.0	0.004	1702	
BC2K-43	25.0	31.5	0.006	1703	
BC2K-43	31.5	32.2	0.215	1704	
BC2K-43	32.2	40.0	0.030	1705	
BC2K-43	40.0	42.1	0.008	1706	
BC2K-43	42.1	45.0	0.008	1707	
BC2K-43	45.0	50.0	0.000	1708	
BC2K-43	50.0	55.0	0.000	1709	
BC2K-43	55.0	62.3	0.000	1710	
BC2K-43	62.3	68.8	0.004	1711	
BC2K-43	68.8	74.0	0.001	1712	
BC2K-43	74.0	79.5	0.001	1713	
BC2K-43	79.5	85.0	0.004	1714	
BC2K-43	85.0	90.0	0.006	1715	
BC2K-43	90.0	100.0	0.005	1716	
BC2K-43	100.0	113.0	0.001	1717	
BC2K-43	126.0	132.7	0.002	1718	
BC2K-43	143.5	147.3	0.003	1719	
BC2K-43	154.6	156.2	0.003	1722	
BC2K-43	156.2	161.0	0.000	1723	
BC2K-43	161.0	166.5	0.003	1724	
BC2K-43	171.0	174.5	0.000	1725	
BC2K-43	187.8	193.3	0.000	1726	
BC2K-43	215.8	221.0	0.000	1727	
BC2K-43	221.0	226.7	0.000	1728	
BC2K-43	233.0	240.0	0.000	1729	
BC2K-43	240.0	243.0	0.000	1730	
BC2K-43	243.0	249.2	0.000	1731	
BC2K-43	249.2	255.8	0.001	1732	
BC2K-43	255.8	260.0	0.000	1733	
BC2K-43	260.0	263.7	0.000	1734	
BC2K-43	263.7	270.0	0.000	1735	
BC2K-43	270.0	276.9	0.000	1736	
BC2K-43	276.9	290.0	0.001	1737	
BC2K-43	376.5	385.6	0.009	1739	
BC2K-43	526.2	527.2	0.000	1742	
BC2K-44	10.0	20.0	0.004	1743	A004745
BC2K-44	20.0	30.0	0.001	1744	
BC2K-44	30.0	40.0	0.001	1745	
BC2K-44	40.0	50.0	0.002	1746	
BC2K-44	50.0	60.0	0.001	1747	
BC2K-44	60.0	70.0	0.000	1748	
BC2K-44	70.0	80.0	0.000	1749	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-44	80.0	90.2	0.000	1750	
BC2K-44	90.2	93.5	0.003	1751	
BC2K-44	93.5	95.5	0.000	1752	
BC2K-44	95.5	96.5	0.409	1753	
BC2K-44	96.5	96.9	0.031	1754	
BC2K-44	96.9	99.5	0.001	1755	
BC2K-44	99.5	100.6	0.043	1756	
BC2K-44	100.6	101.6	0.004	1757	
BC2K-44	101.6	102.8	0.001	1758	
BC2K-44	102.8	103.3	0.615	1759	
BC2K-44	103.3	113.3	0.025	1760	
BC2K-44	113.3	118.4	0.010	1761	
BC2K-44	118.4	119.5	0.195	1762	
BC2K-44	119.5	121.7	0.010	1766	
BC2K-44	121.7	126.5	0.015	1767	
BC2K-44	126.5	127.0	0.017	1768	
BC2K-44	127.0	132.4	0.002	1769	
BC2K-44	132.4	137.6	0.001	1770	
BC2K-44	137.6	142.2	0.001	1774	
BC2K-44	142.2	142.7	0.001	1775	
BC2K-44	155.1	164.0	0.000	1776	
BC2K-44	193.2	200.8	0.000	1777	
BC2K-44	200.8	203.0	0.000	1778	
BC2K-44	203.0	205.3	0.000	1779	
BC2K-44	205.3	208.8	0.000	1780	
BC2K-44	208.8	211.8	0.000	1781	
BC2K-44	220.0	227.0	0.001	1782	
BC2K-44	227.0	232.2	0.000	1783	
BC2K-44	232.2	235.6	0.001	1784	
BC2K-44	249.5	254.0	0.000	1785	
BC2K-44	254.0	259.0	0.000	1786	
BC2K-44	259.0	266.0	0.000	1787	
BC2K-45	25.0	30.2	0.003	1824	A004801
BC2K-45	30.2	35.0	0.006	1825	
BC2K-45	35.0	45.0	0.018	1826	
BC2K-45	45.0	50.0	0.002	1827	
BC2K-45	50.0	55.0	0.001	1828	
BC2K-45	55.0	60.0	0.001	1829	
BC2K-45	60.0	66.0	0.001	1830	
BC2K-45	66.0	70.0	0.000	1831	
BC2K-45	70.0	75.0	0.000	1832	
BC2K-45	75.0	80.0	0.001	1833	
BC2K-45	80.0	85.0	0.000	1834	
BC2K-45	85.0	90.0	0.004	1835	
BC2K-45	90.0	95.0	0.001	1836	
BC2K-45	95.0	100.0	0.000	1837	
BC2K-45	100.0	110.0	0.000	1838	
BC2K-45	110.0	115.0	0.001	1839	
BC2K-45	115.0	120.0	0.001	1840	
BC2K-45	120.0	125.0	0.000	1841	
BC2K-45	125.0	130.0	0.000	1842	
BC2K-45	130.0	135.0	0.000	1843	
BC2K-45	135.0	140.0	0.000	1847	
BC2K-45	140.0	150.0	0.000	1848	
BC2K-45	150.0	160.0	0.000	1849	
BC2K-45	175.3	180.0	0.001	1850	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-45	180.0	185.0	0.001	1851	
BC2K-45	185.0	190.0	0.001	1852	
BC2K-45	291.5	296.0	0.000	1853	
BC2K-45	296.0	300.0	0.001	1854	
BC2K-45	300.0	305.0	0.000	1855	
BC2K-45	305.0	310.0	0.003	1856	
BC2K-45	310.0	315.0	0.001	1857	
BC2K-45	315.0	320.0	0.001	1858	
BC2K-45	445.0	450.0	0.000	1859	
BC2K-45	450.0	455.0	0.000	1860	
BC2K-45	455.0	460.0	0.000	1861	
BC2K-45	550.0	555.0	0.000	1862	
BC2K-45	555.0	560.0	0.000	1864	
BC2K-45	560.0	565.0	0.000	1865	
BC2K-45	565.0	570.0	0.000	1866	
BC2K-46	222.8	230.0	0.000	1908	A004895
BC2K-46	230.0	235.0	0.002	1909	
BC2K-46	235.0	240.0	0.000	1910	
BC2K-46	240.0	245.0	0.000	1911	
BC2K-46	245.0	250.0	0.000	1912	
BC2K-46	250.0	255.0	0.000	1913	
BC2K-46	255.0	260.0	0.000	1914	
BC2K-46	260.0	265.0	0.001	1915	
BC2K-46	265.0	270.0	0.000	1916	
BC2K-46	270.0	275.0	0.000	1917	
BC2K-46	329.4	333.4	0.002	1919	
BC2K-46	344.2	348.6	0.007	1918	
BC2K-47	199.0	204.0	0.001	1867	A004755
BC2K-47	204.0	209.0	0.006	1868	
BC2K-47	209.0	214.0	0.008	1869	
BC2K-47	214.0	219.0	0.069	1870	
BC2K-47	219.0	222.0	0.155	1871	
BC2K-47	222.0	224.2	0.031	1872	
BC2K-47	235.0	240.0	0.012	1873	
BC2K-47	240.0	245.0	0.001	1874	
BC2K-47	245.0	251.5	0.006	1875	
BC2K-47	310.0	315.0	0.001	1877	
BC2K-47	315.0	320.0	0.013	1878	
BC2K-47	320.0	323.5	0.001	1879	
BC2K-47	330.0	336.0	0.002	1881	
BC2K-48	238.4	246.2	0.000	1883	A004823
BC2K-48	246.2	251.0	0.000	1884	
BC2K-48	251.0	255.0	0.001	1885	
BC2K-48	255.0	259.0	0.006	1886	
BC2K-48	259.0	265.0	0.001	1887	
BC2K-48	265.0	268.0	0.001	1888	
BC2K-48	268.0	272.5	0.001	1889	
BC2K-48	272.5	275.0	0.000	1890	
BC2K-48	275.0	280.0	0.000	1891	
BC2K-48	280.0	285.0	0.000	1892	
BC2K-48	285.0	290.0	0.000	1893	

Drill Hole	From (ft)	To (ft)	Assay (oz/st)	Sample No.	Assay Certificate No.
BC2K-48	290.0	295.0	0.001	1894	
BC2K-48	295.0	300.0	0.001	1895	
BC2K-48	300.0	305.0	0.000	1896	
BC2K-48	305.0	310.0	0.000	1897	
BC2K-48	310.0	315.5	0.001	1898	
BC2K-48	315.5	320.0	0.001	1899	
BC2K-48	320.0	326.0	0.001	1900	
BC2K-48	326.0	329.5	0.008	1901	
BC2K-48	329.5	333.0	0.001	1902	
BC2K-48	333.0	335.5	0.007	1903	
BC2K-48	335.5	340.0	0.001	1904	
BC2K-48	340.0	347.0	0.001	1905	

APPENDIX VII

Prospector Sample Descriptions and Detailed Figures

North West Side of Cow Mountain (First / Second Creek Samples)

172369 – Grab of rock from outcrop located 900 feet up first creek's south bank. The rock is a light coloured, crenulated, quartz sericite phyllite with dark interleaves. No pyrite is seen. This outcrop where sampled, strikes at 310° with a dip to the south west at 20° to flat.

172370 – Grab sample of rock taken from first creek at the 1280 foot (390.1m) mark. Sample consists of sericite phyllite with up to 2% pyrite chipped from large slabs found in the creek itself. Due to the large size and angular shapes of the slabs leads me to believe they are locally derived.

172371 – Soil sample collected 100 feet (30.5m) south of 172369. Tan coloured soil.

172372 – Soil sample collected 50 feet (15.25m) below and same side of stream as 172369 was taken. Sample was collected from a large fault gouge system but its strike and attitude could not be determined. Tan and grey coloured soil.

172373 – Soil sample collected along the ditch-line of the highway on the west side of Jack of Clubs lake at a point 150 feet (45.7m) north of the turn off to the second campsite area from Wells. Brown soil.

172374 – Soil sample collected 30 feet (9.1m) north of 172375. Tan soil.

172375 – Soil sample collected where second creek comes out from the ground. This soil was collected in the creek itself. Tan soil.

172376 – Soil sample collected 20 feet (6.1m) south of 172375. Rusty soil.

Pan Orvana Grid Prospecting and Soil Samples

172377 – Soil sample recheck of PO station 4500E 5000N (CGQM grid 11019E 3554N) Tan soil.

172378 – Soil sample collected 40 feet (12.2m) up slope from 172377. Tan soil.

172379 – Soil sample collected 50 feet (15.2m) down slope from 172377. Tan soil.

172380 – Soil sample recheck of PO station 4400E 5050N (CGQM grid 10706E 3402N) Tan soil.

172381 – Soil sample collected 40 feet (12.2m) north of 172380. Reddish soil.

172382 – Soil sample collected 80 feet (24.4m) north of 172380. Reddish soil.

172383 – Soil sample collected 120 feet (36.6m) north of 172380. Reddish soil.

172384 – Soil sample collected 160 feet (48.8m) north of 172380. Reddish soil.

172385 – Soil sample collected 40 feet (12.2m) south of PO station 4300E 5100N (CGQM grid 10458E 3335N). Yellow soil.

172386 – Soil sample recheck of PO station 4300E 5100N (CGQM grid 10458E 3335N). Yellow soil.

172387 – Soil sample collected 40 feet (12.2m) north of 172386. Reddish soil.

172388 – Soil sample collected 80 feet (24.4m) north of 172386. Yellow soil.

172389 – Soil sample collected on the road 150 feet (45.7m) below 172388. Rusty soil.

172390 – Soil sample collected 32 feet (9.8m) from the end of the road that passes between PO grid stations 4500E 5000N and 4400E 5050N. Rusty soil.

172391 – Soil sample recheck of PO station 4400E 5000N (CGQM grid 10738E 3258N). Tan soil.

172392 – Soil sample recheck of PO station 4400E 4960N (CGQM grid 10828E 3176N). Tan soil.

172393 – Soil sample collected from a road at a point 1050 feet (320m) south of the 1200 portal. Tan soil with pieces of bleached rock and quartz.

172394 – Soil sample collected on the road 30 feet (9.1m) north of 172393. Tan soil with pieces of bleached rock and quartz.

Lowhee Creek

171351 – L/00+1 Soil sample collected on the east slope 35m above Lowhee creek in an area located 150m downstream from the confluence of Watson's gulch and Lowhee creek. Soil sample is yellow in colour.

171352 – L/00+2 Soil sample collected 15m northwest of 171351 at the same elevation also yellow in color.

171353 – L/00+3 Soil sample collected 60m south of the highest point of the groundhog trail. Sample of rusty red soil.

171354 – L/00+4 Soil sample collected on the east slope 25m above Lowhee creek in an area located 250m below the confluence of Watson's gulch and Lowhee creek. Rusty red and yellow gouge.

171355 – L/00+5 Soil sample collected 15m above 171354. Soil is yellow in colour.

171356 – L/00+6 Soil sample collected on east slope of Lowhee creek 60m north of 171352. Soil is red and yellow.

171357 – L/00+7 Soil sample collected 35m above Lowhee creek along the east slope. This sample is located 150m north of 171357.

171372 – L/00+8 Soil sample collected 20m east of the most southerly portion of the Black Bull Vein. Soil is yellowish in colour.

171025 – LR/00+1 Channel sample of rock across 1m, collected 25m above Lowhee creek along its east slope at a point 150m upstream from the end of the road to Wells (Wilf's place). Sericite schist, minor quartz lenses, hematite dust pockets, tan to light green alteration with <1% pyrite.

171026 – LR/00+2 Channel sample of rock across 1.5m collected 50m downstream from the confluence of Watson's gulch and Lowhee creek. Quartz vein about 45cm wide with remainder of sample being a highly oxidized sericite schist with hematite and <1% pyrite.

171027 – LR/00+3 Channel sample of rock across 1m collected 20m above Lowhee creek at a point located 250m below the confluence of Watson's gulch and Lowhee creek. Sericite schist, quartzite, hematite and <1% pyrite.

171028 – LR/00+4 Channel sample of rock across 1m. Sample site is located 14m north of Ned 11 and 12 final post. Sample was taken at a creek level on the west side of Lowhee creek. Carbonate altered limestone-dolomite rusty red in colour with distinct laminations, sericite chlorite and 2% pyrite (GP Figure 1).

171029 – LR/00+5 Channel sample of rock across 1m located adjacent to 171028. Same rock type.

171030 – LR/00+6 Channel sample of rock across 1m located adjacent to 171029. Same rock type.

171031 – LR/00+7 Channel sample of rock across 0.4m located adjacent to 171030. Same rock type with 2% pyrite. Samples 171028-171031 were collected from a zone striking 305° with a vertical dip.

171032 – LR/00+8 Channel sample of rock across 1m located on west side of Lowhee creek about 30m upstream from Ned 11 and 12 final post. Rusty red surface oxidation with <1% pyrite. Sample was collected at creek level.

171033 – LR/00+9 Channel sample of rock across 1m located on west side of Lowhee creek about 30m upstream from 171032. This sample was collected 4m above creek level. Reddish brown dolomite with quartz stringers, sericite, hematite and <1% pyrite.

171034 – LR/00+10 Channel sample of rock across 1m collected on east slope of Lowhee creek at a point 40m east of the Ned 9 and 10 final post. This is the first of a series of 9 samples gathered in a numbered sequence across the strike of a large zone of alteration exhibiting a phyllitic lineation. Sample consists of quartzite, sericite, hematite, chlorite and <1% pyrite. The zone strikes at 310° degrees with a dip to the northeast of 45° (GP Figure 2).

171035 – LR/00+11 Channel sample of rock across 1m collected adjacent to 171034 going east. Same rock type and mineralization as 171034.

171036 – LR/00+12 Channel sample of rock across 1m collected adjacent to 171035 going east. Same rock type and mineralization as 171034.

171037 – LR/00+13 Channel sample of rock across 1m collected adjacent to 171036 going east. Same rock type and mineralization as 171034.

171038 – LR/00+14 Channel sample of rock across 1m collected adjacent to 171037 going east. Same rock type and mineralization as 171034.

171039 – LR/00+15 Channel sample of rock across 1m collected adjacent to 171038. This sample consists of a 0.75m wide black quartzite seam with numerous limey filled vugs and fractures, along with a 0.25m wide quartz lens filled shear zone on the bottom. <1% pyrite.

171040 – LR/00+16 Channel sample of rock across 1m collected adjacent to 171039 going east.

Same rock type and mineralization as 171034. Laminations are very thin at this point.

171041 – LR/00+17 Channel sample of rock across 1m collected adjacent to 171040 going east. Same rock type and mineralization as 171034. Laminations become regular again.

171042 – LR/00+18 Channel sample of rock across 1m collected adjacent to 171041 going east. Same rock type and mineralization as 171034. More rusty red oxidation is visible at this point.

171043 – LR/00+19 Channel sample of rock collected on road 60m east of the Canusa mine dump. Carbonate altered sericite schist with pods and veinlets quartz, hematite and <1% pyrite.

171044 – LR/00+20 Channel sample of rock across 1m collected 60m east of the most southerly portion of the Black Bull quartz vein. Carbonate altered sericite schist with minor pods and lenses of quartz, <1% pyrite. This is the first of a series of four rock samples gathered on the east slope of Lowhee creek (GP Figure 3).

171045 – LR/00+21 Channel sample of rock across 1m collected adjacent to 171044 going north. Same rock type and mineralization as 171044.

171046 – LR/00+22 Channel sample of rock across 1m collected adjacent to 171045 going north. Same rock type and mineralization as 171044.

171047 – LR/00+23 Channel sample of rock across 1m collected adjacent to 171046 going north. Same rock type and mineralization as 171044.

171048 – LR/00+24 Channel sample of rock across 1m collected 20m above 171353 going east. Carbonate altered sericite schist, quartzite, hematite, chlorite and <1% pyrite

171049 – LR/00+25 Channel sample of rock across 1.4m collected 3m above 171048 on the east slope of Lowhee creek. Carbonate altered sericite schist, very rusty with a surface appearance similar to a gouge. Chlorite, hematite and <1% pyrite.

171050 – LR/00+26 Channel sample of rock collected on the east slope of Lowhee creek at a point 25m below 171356. Carbonate altered sericite schist, 50% quartzite with hematite blebs and streaks, 1% pyrite.

171358 – LR/00+27 Channel sample of rock across 1m collected on the east slope of Lowhee creek at a point 35m southeast of 171042. Rusty red gouge.

171359 – LR/00+28 Channel sample of rock across 1m collected on the east slope of Lowhee creek at a point 20m southeast of 171358. Sample consists of 0.25m rusty red gouge and 0.75m altered dolomite with chlorite and sericite.

171360 – LR/00+29 Channel sample of rock across 1m collected adjacent to 171359 going east. Rusty red gouge.

171361 – LR/00+30 Grab sample of rock collected 3m above 171360. Grey and mauve coloured phyllite mineralized with garnets and 1% pyrite.

171366 – LR/00+31 Grab sample collected 20m east of the most southerly tip of the Black Bull vein. Altered dolomite with yellowish gouge, <1% pyrite.

171367 – LR/00+32 Grab sample of quartz from footwall side of Black Bull vein on its most southerly portion. Quartz sericite, pyrrhotite, hematite and 1% pyrrhotite and pyrite.

171368 – LR/00+33 Channel sample of rock across 1m starting form footwall going northeast. This sample was the first of a series of four channel samples colleted off the Black Bull quartz vein at a point located 15m northwest of its most southerly visible portion. Quartz, sericite and hematite. (GP Figure 4)

171369 – LR/00+34 Channel sample of quartz across 1m adjacent to 171368 going northeast. Quartz, sericite and hematite.

171370 – LR/00+35 Channel sample of quartz across 1m adjacent to 171369 going northeast. Quartz, sericite and hematite.

171371 – LR/00+36 Channel sample of quartz across 1m adjacent to 171370 going northeast. Quartz sericite hematite and 1% pyrite and pyrrhotite.

171362 – LR/00+37 Grab sample of rock off mine dump located about 100m below BC vein shaft. Quartz in foliated argillite with 10% pyrite.

171363 – LR/00+38 Grab sample of rock off the same mine dump as 171362. sample contained 20% pyrite in foliated quartz and argillite.

171399 – LR/00+39 Grab sample of rock off mine dump on the edge of the timber directly across from Watson's gulch. Medium to dark coloured phyllite of quartzite and argillite with 2% pyrite.

171400 – LR/00+40 Grab sample by Richard Hall off same mine dump as 171399. Light coloured phyllite with quartzite, sericite and 5% pyrite.

Stout's Gulch

172395 – Grab sample of yellow gouge taken along Stout's gulch road at a point 175 feet (53.3m) above the confluence of Emory creek and Stout's gulch. This gouge consists mainly of ground up pieces of quartz with minor pyrite cubes set in a yellow clay matrix. This clay is indicative of a fault system at this location, but its strike and attitude could not be determined at this time.

172396 – Rock grab sample of a large dolomite, limestone and quartz boulder with 3% pyrite. Sample was taken 100 feet (30.5m) upstream from CGQM station L21800E 1550N in Emory creek.

172625 – Rock channel sample collected across a 30" (0.75m) quartz filled shear zone. This sample site is located 38 feet (11.6m) south of CGQM station L14400E 3700N. Shear consists of quartz, sericite, hematite and 5% pyrite. Strike 290° with a vertical dip. (Lowhee creek)

172626 – Rock grab sample collected 185 feet (56.4m) north of CGQM station L14400E 3800N, Lowhee creek. Altered light coloured phyllite with sericite and 3% pyrite.




Figure 1 Sept 2000 GPP

Lowhee creek




Figure 2 Sept 2000 GPP





Figure 3 Sept 2000 GPP

Scale 1m 2m

Scale 1m 2m 3m

Figure 1 Sept 2000 GPP



APPENDIX VIII

APPENDIX VIII

Statement of Expenditures

International Wayside Gold Mines Ltd.

Head Office
305-455 Granville Street
Vancouver, B.C., V6C 1T1

Phone: (604) 669-6463
Fax: (604) 669-3041

Wells Field Office
P.O. Box 247, 12422 Barkerville Hwy.
Wells, B.C., V0K 2R0

Phone: (250) 994-3337
Fax: (250) 994-3338

Year 2000 Geotechnical Cost Summary

Diamond Drilling	$ 440,150.65
Geological Consulting	439,517.45
Engineering	39,913.61
Geophysical/Geochemical	147,694.76
Environmental & Permitting	632,738.28
Underground	28,917.48
Administrative	27,241.58
Core Handling	73,199.13
Assays	99,024.08
Year 2000 Total	**$1,928,397.02**

See spreadsheets for itemized details

YTD 2000 Drill & Labour Costs

Period	Gagnon	Harris	Hartford	Nestel	Johnson	Cright	Misc. Help.	Equip.Rent	Bits/Parts	Wilco	Fuel	Core Boxes	Reclaim	Mud/Lube	First Aid	Misc	MONTHLY & CUMULATIVE TOTAL
Jan-00								$5,000.00		$3,333.33				$255.68			$8,589.01
Feb-00	$2,390.04	$1,300.79						$5,000.00	$1,935.64	$3,333.33	$1,785.56			$546.50			$16,291.86
Mar-00		$2,603.57						$5,000.00	$12,967.77	$7,556.00	$4,650.16	$1,116.98		$546.50			$34,440.98
Apr-00	$3,127.47	$1,619.79		$2,017.65			$1,729.41	$5,000.00	$31,476.12	$15,029.74	$3,969.90	$2,820.95		$546.50	$320.00		$67,657.53
May-00	$3,787.26	$3,263.53		$2,816.59	$1,654.30		$1,140.24	$5,000.00	$17,105.91	$14,373.23	$4,078.16		$3,425.20	$546.50	$960.00		$58,150.92
Jun-00	$2,413.95	$1,722.38		$1,799.22	$379.81			$5,000.00	$14,019.49					$546.50	$470.53	$5,233.64	$31,585.52
Jul-00	$2,307.12	$5,706.16		$1,745.74	$2,941.82	$2,418.97	$343.40	$5,000.00	$7,188.25		$1,865.97	$1,194.66	$4,875.00	$511.36			$36,098.45
Aug-00		$3,389.60			$1,125.78	$1,726.56		$7,624.00	$6,507.93	$9,182.37	$7,461.92	$2,389.32	$5,389.93	$255.68			$45,053.09
Sep-00	$320.00	$6,965.00	$3,905.00		$165.00	$4,717.50		$7,625.00	$4,878.91		$4,249.16		$540.00	$255.68	$584.00		$34,205.25
Oct-00	$1,285.00	$7,324.00	$5,230.00		$45.00	$4,492.00	$3,093.50	$7,625.00	$16,212.24		$3,512.22		$1,380.00	$511.36	$2,389.69		$53,100.01
Nov-00	$4,976.75	$7,300.00	$4,721.75		$1,212.50	$4,801.25	$2,296.25	$7,625.00	$2,291.74		$3,110.08		$5,187.00	$703.34	$2,425.00	$423.37	$47,074.03
Dec-00								$7,625.00					$279.00				$7,904.00
Total	**$20,607.59**	**$41,194.82**	**$13,856.75**	**$8,379.20**	**$7,524.21**	**$18,156.28**	**$8,602.80**	**$73,124.00**	**$114,584.00**	**$52,808.00**	**$34,683.13**	**$7,521.91**	**$21,076.13**	**$5,225.60**	**$7,149.22**	**$5,657.01**	**$440,150.65**

2000 IWA YTD Geological Consulting

Period	Reid, R.E.	Geosim	R.D. Hall	Geologic	Panterra	VOX Image	K. Lord	Paragon	Eagle	Giroux	BC Research	A. Justason	T.C. Scott	Prospecting Polischuck	Meals & Accom.	MONTHLY & CUMULATIVE TOTAL
Jan-00																
Feb-00	$2,939.99		$1,854.14													$4,794.13
Mar-00		$8,252.38													$750.00	$9,002.38
Apr-00	$12,650.75	$3,050.10	$14,811.71	$953.94	$3,220.00	$2,268.40									$1,600.00	$38,554.90
May-00		$4,614.38	$7,594.45	$11,683.98	$18,810.90	$5,869.95	$5,238.44	$749.00							$3,800.00	$58,361.10
Jun-00			$12,867.74		$8,380.36	$5,510.50	$2,925.00		-$14,400.00						$3,800.00	$19,083.60
Jul-00			$8,123.40		$13,228.25	$3,049.50	$5,400.00		$29,338.50	$10,651.19	$1,647.00				$3,800.00	$75,237.84
Aug-00			$16,243.04	$10,389.05	$8,325.50		$3,150.00		$1,757.48		$180.00	$2,170.00			$3,800.00	$46,015.07
Sep-00			$6,657.26	$11,452.74	$12,787.30		$5,537.25		$28,991.65			$620.00		$3,301.00	$3,800.00	$73,147.20
Oct-00			$11,701.38	$12,991.60	$11,407.00		$4,865.00						$1,125.00	$2,640.00	$3,800.00	$48,529.98
Nov-00			$4,537.46		$16,098.75		$6,018.75		$15,408.00				$4,006.64		$1,600.00	$47,669.60
Dec-00			$2,856.73	$478.00	$5,216.25		$6,179.25			$4,391.42						$19,121.65
Total	**$15,590.74**	**$15,916.86**	**$87,247.31**	**$47,949.31**	**$97,474.31**	**$16,698.35**	**$39,313.69**	**$749.00**	**$61,095.63**	**$15,042.61**	**$1,827.00**	**$2,790.00**	**$5,131.64**	**$5,941.00**	**$26,750.00**	**$439,517.45**

2000 YTD Engineering Costs

Period	Elixir	Monad	CSFM	Unit E.E.	Beacon Hill	Cariboo Forest Cons.	Cumulative Total
Jan-00							
Feb-00	$2,880.00		$6,933.00				$9,813.00
Mar-00				$3,889.50			$3,889.50
Apr-00	$10,029.81	$3,781.00	$1,396.39				$15,207.20
May-00	$6,640.96		$923.28			$418.50	$7,982.74
Jun-00	$96.17				$2,925.00		$3,021.17
Jul-00							
Aug-00							
Sep-00							
Oct-00							
Nov-00							
Dec-00							
TOTAL	**$19,646.94**	**$3,781.00**	**$9,252.67**	**$3,889.50**	**$2,925.00**	**$418.50**	**$39,913.61**

2000 IWA YTD Geophysical Costs

Period	Blue Cedar	SJ	E. Hall	Scott	C. Hall	Sabre	CUMULATIVE TOTAL
Jan-00							
Feb-00							
Mar-00							
Apr-00							
May-00							
Jun-00							
Jul-00	$500.00	$2,165.12	$171.29				$2,836.41
Aug-00			$14.97				$14.97
Sep-00					$555.00	$26,840.89	$27,395.89
Oct-00				$44,138.99		$61,673.48	$105,812.47
Nov-00		$321.00		11314.02			$11,635.02
Dec-00							
Total	**$500.00**	**$2,486.12**	**$186.26**	**$55,453.01**	**$555.00**	**$88,514.37**	**$147,694.76**

2000 YTD Environmental Monitoring & Permitting Costs

Period	Knight Piesold	Cariboo Envirotech	J. Harris	Archaeo Research	Arcas Consulting	Mehling	Cantest	K. Pollock	T. Church	Cumulative Total
Jan-00	$7,006.90	$13,568.03	$1,600.00					$479.60		$22,654.53
Feb-00	$77,602.41		$1,600.00					$1,913.32		$81,115.73
Mar-00	$95,301.80		$6,600.00					$4,837.20		$106,739.00
Apr-00	$13,987.68	$7,583.63	$5,378.27				$8,888.00	$525.00		$36,362.58
May-00	$44,919.85	$5,244.28	$5,581.63			$950.00	$9,196.90	$1,587.50		$67,480.16
Jun-00	$72,252.41	$12,876.79	$3,708.20							$88,837.40
Jul-00	$54,023.29	$1,933.93	$2,787.76						$2,182.50	$60,927.48
Aug-00	$46,904.34	$17,390.09	$1,700.00	$36,666.10			$6,766.57		$2,340.00	$111,767.10
Sep-00	$7,528.74		$1,250.00		$10,998.00			$1,594.20	$3,888.75	$25,259.69
Oct-00	$5,876.90		$1,611.13					$175.00	$2,011.50	$9,674.53
Nov-00	$5,806.91	$4,280.00						$200.00	$2,111.25	$12,398.16
Dec-00	$5,500.00			$2,554.96					$1,466.96	$9,521.92
Total	**$436,711.23**	**$62,876.75**	**$31,816.99**	**$39,221.06**	**$10,998.00**	**$950.00**	**$24,851.47**	**$11,311.82**	**$14,000.96**	**$632,738.28**

2000 IWA YTD Underground Costs

Period	Blagdon	Mulholland	MONTHLY & CUMULATIVE TOTAL
Jan-00			
Feb-00			
Mar-00			
Apr-00			
May-00			
Jun-00			
Jul-00	$7,260.00	$3,520.00	$10,780.00
Aug-00	$7,879.98	$3,360.00	$11,239.98
Sep-00	$3,465.00	$3,432.50	$6,897.50
Oct-00			
Nov-00			
Dec-00			
Total	**$18,604.98**	**$10,312.50**	**$28,917.48**

2000 IWA YTD Administrative Costs - Wells Field Office

Period	Macpherson	L. Hartford	L. Phinney	CUMULATIVE TOTAL
Jan-00	$200.00			$200.00
Feb-00				
Mar-00	$1,978.58			$1,978.58
Apr-00	$3,300.00			$3,300.00
May-00	$3,226.00			$3,226.00
Jun-00	$1,997.00			$1,997.00
Jul-00	$3,500.00			$3,500.00
Aug-00	$1,750.00			$1,750.00
Sep-00	$1,750.00	$260.00		$2,010.00
Oct-00	$1,750.00	$250.00	$120.00	$2,120.00
Nov-00	$3,500.00		$160.00	$3,660.00
Dec-00	$3,500.00			$3,500.00
Total	**$26,451.58**	**$510.00**	**$280.00**	**$27,241.58**

2000 IWA YTD Non-Geological Core Handling Costs - Includes Sawyers/Splitters

Period	Pawlowicz	Church	Cright	Hipwell	Brown	Landry	Mulholland	Williams	L. Phinney	Union Fence	Wright	Saw Supplies	Assays	MONTHLY & CUMULATIVE TOTAL
Jan-00														
Feb-00												$172.77		$172.77
Mar-00	$918.74											$920.66		$1,839.40
Apr-00		$1,114.08										$4,582.53		$5,696.61
May-00		$2,197.15	$904.03									$910.62		$4,011.80
Jun-00		$924.67		$425.46								$443.76		$1,793.89
Jul-00	$378.73		$1,021.61	$1,420.30	$328.66					$9,566.00	$16,085.37	$1,032.16		$29,832.83
Aug-00		$910.85		$890.16	$380.28							$1,740.06		$3,921.35
Sep-00		$1,211.25		$1,750.00				$335.00				$383.76		$3,680.01
Oct-00				$80.00		$520.00	$520.00				$18,167.64	$889.33		$20,176.97
Nov-00						$1,019.00			$262.50					$1,281.50
Dec-00						$507.00			$285.00					$792.00
Total	**$1,297.47**	**$6,358.00**	**$1,925.64**	**$4,565.92**	**$708.94**	**$2,046.00**	**$520.00**	**$335.00**	**$547.50**	**$9,566.00**	**$34,253.01**	**$11,075.65**		**$73,199.13**

APPENDIX IX

ASSAY CERTIFICATES

PART 1 - DIAMOND DRILL SAMPLE ASSAY CERTIFICATES

PART 1

ACME
Analytical Laboratories Ltd.

ISO 9002 REGISTERED

852 East Hastings Street, Vancouver, British Columbia, Canada V6A 1R6
Telephone: (604) 253-3158 • Facsimile: (604) 253-1716 • Toll free: 1-800-990-ACME (2263) • e-mail: [redacted]
info@acmelab.com

June 28, 2000

The following describes key points of Acme Labs quality system for sample preparation and analysis:

- Arriving sample shipment is inspected for completeness and soundness.
- Information is entered in to LIMS (Laboratory Information Management System) indicating the file number, client information, sample numbers, type of analysis, etc.)
- LIMS generates a Confirmation of Request for Analytical Work that is sent to the client specifying the number of samples, type of analysis to be done, estimated date of completion and file number assigned to the job.
- LIMS generates worksheets and labels identifying samples, client information, type of analysis to be undertaken, file number, target date, etc. Worksheets accompany samples through all stages of analysis; all staff, equipment and reagents involved are identified in the worksheets. LIMS selects positions for random insertion of quality control (QC) samples:
  - blanks (2 per batch of 34 samples)
  - duplicates (1 or 2 per batch of 34 samples)
  - standard (2 per batch of 34 samples)

  Drill core and sludge samples also include:
  - 1 duplicate from crushed reject (RRE: duplicate) and
  - 1 duplicate from pulp material (RE: duplicate)
- Each sample is inspected by staff trained in recognizing sample types and mineralization to ensure appropriate handling and preparation procedures are used.
- Wet samples are dried at 60C.
- The entire dried sample is crushed to 70% -10 mesh. Sample is then split several times (if necessary) through Jones Riffle Splitter until approximately 250 grams is obtained. Reject samples are stored in a dry warehouse for three months or until client retrieve them or additional storage time is purchased.
- The 250 gram sub-sample is pulverized with disc and puck pulverizer to 95% -150 mesh.
- First sample in sequence is a silica blank carried through from crushing to analysis to measure background contamination. Crushers and pulverizers are calibrated at the beginning of each shift to yield the required parameters. Cleaning procedures for crushing and pulverizing are used between each sample and extra cleaning measures or high-grade equipment are used on mineralized samples.
- Appropriate standards and duplicate pulp splits (RE:) are added to sample sequence during weighing to monitor accuracy and precision of analytical data. Staff inspects sequence and positions of QC samples at all stages of handling to ensure sequence integrity.

- Samples undergo fire assay, (acid digestion for 30 element ICP analysis), reagent blanks for measuring background are also added in the sequence.
- Analytical instruments undergo calibration at the beginning of each shift and calibration checks at the beginning and ending of each data file.
- LIMS acquires results from automated instruments and evaluates accuracy and precision using QC samples, calibration check and verification standards, internal standard spike recoveries, linearity standards, etc. Results are then printed for evaluation by instrument operator. Re-analysis and data adjustment are made where necessary.
- Raw and adjusted data are inspected by Data Verification Person.
- Results from various test are combined and checked by data entry and checking clerks.
- All documents and data are evaluated by a B.C. Certified Assayer to ensure work complies with request from client and results meet quality criteria.

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604) 253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Standard Drilling PROJECT CARIBOO 2000 File # A000659

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Au** gm/mt
B 169094	1.72
B 169095	10.70
B 169096	.10
B 169097	1.03
B 169098	4.79
B 169099	3.91
B 169100	18.96
B 169101	.47
B 169102	2.44
RE B 169102	2.47
RRE B 169102	2.58
B 169103	30.08
B 169104	6.83
B 169105	15.76
B 169106	1.50
B 169107	1.03
STANDARD AU-1	3.40

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: FEB 29 2000 DATE REPORT MAILED: March 2/2000 SIGNED BY. C. D. TOYE, C.LEONG WANG; CERTIFIED B.C. ASSAYERS

All results considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A000825

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Au** ppb
B 169601	3242
B 169602	697
B 169603	8161
B 169604	2871
B 169605	6623
B 169606	55
B 169607	114
B 169608	21
B 169609	202
B 169610	106
RE B 169610	114
RRE B 169610	118
B 169611	86
B 169612	109
B 169613	1092
B 169614	2706
B 169615	15
B 169616	2502
B 169617	50
B 169618	155
B 169619	60
B 169620	471
B 169621	33147
B 169622	10353
RE B 169622	9293
RRE B 169622	10845
B 169623	5492
B 169624	63
B 169625	28
B 169626	4311
STANDARD AU-R	458

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: CORE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAR 14 2000 DATE REPORT MAILED: March 22/2000 SIGNED BY: ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

Assay in progress for gold > 1000 ppb

All results considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

DF/FA

ACME ALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST ANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(6 253-1716
(ISO 9002 Accredited Co.)

WHOLE ROCK ICP ANALYSIS

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A000825R

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Ba %
B 169612	.27
B 169613	.32
RE B 169613	.32

GROUP 4A - 0.200 GM SAMPLE BY LIBO2 FUSION, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE PULP
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAR 17 2000 DATE REPORT MAILED: March 27/2000 SIGNED BY. D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A000825R2

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Au** oz/t
B 169601	.097
B 169603	.274
B 169604	.087
B 169605	.207
B 169613	.034
B 169614	.087
B 169616	.077
B 169621	1.395
B 169622	.315
B 169623	.161
RE B 169623	.164
B 169626	.133
STANDARD AU-1	.102

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE PULP
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAR 22 2000 DATE REPORT MAILED: March 28/2000 SIGNED BY: C. Leong D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE (604) 253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD 2K File # A00112 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Au** gm/mt
B 169475	.03
B 169476	.55
B 169477	.41
B 169478	.31
B 169479	.58
B 169480	7.11
B 169481	.08
B 169482	.16
B 169483	1.12
B 169484	54.26
B 169485	1.61
RE B 169485	1.65
RRE B 169485	1.64
B 169486	2.17
B 169487	.40
B 169488	1.61
B 169489	.23
B 169490	.19
B 169491	.07
B 169492	.02
B 169493	.04
B 169494	.05
B 169495	.02
B 169496	.02
B 169497	.03
RE B 169497	.03
RRE B 169497	.04
B 169498	.02
B 169499	.01
B 169500	.05
B 169786	<.01
B 169787	<.01
B 169788	<.01
B 169789	<.01
STANDARD AU-1	3.27

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns

DATE RECEIVED: APR 11 2000 DATE REPORT MAILED: April 18/2000 SIGNED BY. ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

SAMPLE#	Au** gm/mt
B 169790	.01
B 169791	.02
B 169792	.52
B 169793	<.01
B 169794	<.01
B 169795	<.01
B 169796	<.01
B 169797	<.01
B 169798	<.01
B 169799	<.01
B 169800	<.01
RE B 169800	<.01
RRE B 169800	<.01
B 169801	<.01
B 169802	<.01
B 169803	<.01
B 169804	<.01
B 169805	<.01
B 169806	<.01
B 169807	<.01
B 169808	<.01
B 169809	.27
B 169810	<.01
B 169811	<.01
B 169812	.02
RE B 169812	.02
RRE B 169812	.02
B 169813	<.01
B 169814	<.01
B 169815	<.01
B 169816	<.01
B 169817	<.01
B 169818	<.01
B 169819	<.01
STANDARD AU-1	3.30

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' are Re[illegible]t Reruns.

All resul[illegible]e considered the confidential property of the client. Acme assumes [illegible] liabilities for actual cost of the analysis onl[illegible].

FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A001008 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Au** gm/mt
B 169731	.09
B 169732	.04
B 169733	.01
B 169734	.01
B 169735	<.01
B 169736	.09
B 169737	.09
B 169738	.04
B 169739	.17
B 169740	.46
B 169741	.05
B 169742	9.73
RE B 169742	9.79
RRE B 169742	10.22
B 169743	2.52
B 169744	6.51
B 169745	2.24
B 169746	3.85
B 169747	16.70
B 169748	76.71
B 169749	87.08
B 169750	26.33
B 169751	23.98
B 169752	16.43
B 169753	36.90
B 169754	33.96
RE B 169754	33.62
RRE B 169754	32.96
B 169755	33.72
B 169756	5.54
B 169757	.74
B 169758	.09
B 169759	.11
B 169760	.07
STANDARD AU-1	3.42

GROUP 3 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE. ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAR 31 2000 DATE REPORT MAILED: April 7/2000 SIGNED BY: ..... D. TOYE, C.LEONG, J.WANG; CERTIFIED B.C. ASSAYERS

All results considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

SAMPLE#	Au** gm/mt
B 169761	.05
B 169762	.05
B 169763	.03
B 169764	.15
B 169765	.37
B 169766	2.05
B 169767	5.16
B 169768	15.07
B 169769	.65
B 169770	1.44
RE B 169770	1.51
RRE B 169770	1.47
B 169771	4.78
B 169772	.44
B 169773	1.24
B 169774	1.13
B 169775	.81
B 169776	.20
B 169777	1.21
B 169778	.58
B 169779	.30
B 169780	.14
RE B 169780	.14
RRE B 169780	.14
B 169781	.07
B 169782	.22
B 169783	.72
B 169784	.14
B 169785	.16
STANDARD AU-1	3.38

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' are Re[illegible]t Reruns.

All resul[illegible]re considered the confidential property of the client. Acme assumes[illegible] liabilities for actual cost of the analysis on[illegible]

FA

TSL LABORATORIES
#2 – 302 48th Street • Saskatoon, SK • S7K 6A4
P (306) 931-1033 F (306) 242-4717 E tsllab@sk.sympatico.ca

Replicates BC2K-10

CERTIFICATE OF ANALYSIS

SAMPLE(S) FROM International Wayside Gold Mines Ltd.
Box 247 - 2422 Barkerville Highway
Wells, British Columbia
V0K 2R0

REPORT No. 89776

SAMPLE(S) OF Reject

INVOICE #: 10450
P.O.:

Check samples from Acme Analytical Laboratories Ltd.

	Au g/t
B169731	.03
B169732	<.03
B169733	<.03
B169734	<.03
B169735	<.03
B169736	.10/.10
B169737	.03
B169738	<.03
B169739	.07
B169740	.66/.48
B169741	.03
B169742	10.76
B169743	3.28
B169744	6.55/6.24
B169745	2.69
B169746	4.55/4.17
B169747	16.17/16.38
B169748	111.4/111.3
B169749	118.8/120.5
B169750	29.79/29.69

COPIES TO: N. Reid
INVOICE TO: Intl. Wayside Gold - Wells,BC

Apr 20/00

SIGNED _____

04/22/00 11:51 FAX 1 306 242 4717 TSL LABORATORIES SIOON 002

TSL LABORATORIES
#2 – 302 48th Street • Saskatoon, SK • S7K 6A4
P (306) 931-1033 F (306) 242-4717 E tsllab@sk.sympatico.ca

CERTIFICATE OF ANALYSIS

SAMPLE(S) FROM International Wayside Gold Mines Ltd.
Box 247 - 2422 Barkerville Highway
Wells, British Columbia
V0K 2R0

REPORT No. S9776

SAMPLE(S) OF Reject

INVOICE #: 10450
P.O.:

	Au g/t
B169751	26.00
B169752	18.00
B169753	39.03/39.14
B169754	35.86/36.03
B169755	32.34/32.24
B169756	5.00/5.17
B169757	.59
B169758	.03
B169759	.03
B169760	<.03
B169761	<.03
B169762	<.03
B169763	<.03
B169764	.03
B169765	.34
B169766	2.41/2.28
B169767	5.62
B169768	19.24/18.76
B169769	.66
B169770	1.72/1.66

COPIES TO: N. Reid
INVOICE TO: Intl. Wayside Gold - Wells,BC

Apr 20/00

SIGNED _____

04/23/00 11:55 FAX 1 306 242 4717 TSL LABORATORIES SIOON 003

TSL LABORATORIES
#2 – 302 48th Street · Saskatoon, SK · S7K 6A4
P (306) 931-1033 F (306) 242-4717 E tsllab@sk.sympatico.ca

CERTIFICATE OF ANALYSIS

SAMPLE(S) FROM International Wayside Gold Mines Ltd.
Box 247 - 2422 Barkerville Highway
Wells, British Columbia
V0K 2R0

REPORT No. 9776

SAMPLE(S) OF Reject

INVOICE #: 10450
P.O.:

	Au g/t
B169771	4.79
B169772	.38
B169773	1.45
B169774	1.38
B169775	.83
B169776	<.03
B169777	.03
B169778	.48
B169779	.03
B169780	.03/.03
B169781	<.03
B169782	.14
B169783	.86
B169784	.14
B169785	.10

COPIES TO: N. Reid
INVOICE TO: Intl. Wayside Gold - Wells,BC

Apr 20/00

SIGNED _____

04/22/00 11:55 FAX 1 306 242 4717 TSL LABORATORIES SIOON 004

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604) 253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A000958 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: NED

SAMPLE#	Au** gm/mt
B 169627	.96
B 169628	.68
B 169629	.03
B 169630	.47
B 169631	2.00
B 169632	1.81
B 169633	7.57
B 169634	.34
B 169635	.07
B 169636	.03
B 169637	<.01
B 169638	<.01
B 169639	<.01
B 169640	<.01
RE B 169640	<.01
RRE B 169640	<.01
B 169641	<.01
B 169642	<.01
B 169643	<.01
B 169644	<.01
RE B 169644	<.01
RRE B 169644	<.01
B 169645	<.01
B 169646	<.01
B 169647	<.01
B 169648	<.01
B 169649	<.01
B 169650	<.01
B 169651	<.01
B 169652	<.01
B 169653	<.01
B 169654	<.01
B 169655	<.01
B 169656	<.01
STANDARD AU-1	3.28

GROUP 4 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE. ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAR 27 2000 DATE REPORT MAILED: April 3/2000 SIGNED BY. . . . . D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only. FA

SAMPLE#	Au** gm/mt
B 169657	<.01
B 169658	<.01
B 169659	<.01
B 169720	.16
B 169721	.48
B 169722	.15
B 169723	.01
B 169724	.03
B 169725	1.76
RE B 169725	1.73
RRE B 169725	1.90
B 169726	.41
B 169727	.79
B 169728	.34
B 169729	.24
B 169730	.59
STANDARD AU-1	3.41

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

ACME ANALYTICAL LABORATORIES LTD. (ISO 9002 Accredited Co.) 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716

ASSAY CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A000958R Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: NED

SAMPLE#	Au** gm/mt
B 169627	.91
B 169628	.70
B 169629	.03
B 169630	.53
B 169631	1.87
B 169632	1.37
B 169633	7.50
B 169634	.31
B 169635	.08
B 169636	.03
B 169637	<.01
B 169638	<.01
B 169639	<.01
B 169640	<.01
RE B 169640	<.01
RRE B 169640	<.01
B 169641	<.01
B 169642	<.01
B 169643	<.01
B 169644	<.01
RE B 169644	<.01
RRE B 169644	<.01
B 169645	<.01
B 169646	<.01
B 169647	<.01
B 169648	<.01
B 169649	<.01
B 169650	<.01
B 169651	<.01
B 169652	<.01
B 169653	<.01
B 169654	<.01
B 169655	<.01
B 169656	<.01
STANDARD AU-1	3.45

Re assay

GROUP 3 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE. ANALYSIS BY ICP-ES.
- SAMPLE TYPE: PULP
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAY 18 2000 DATE REPORT MAILED: May 19/2000 SIGNED BY. ..D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

DF/FA

SAMPLE#	Au** gm/mt
B 169657	<.01
B 169658	<.01
B 169659	<.01
B 169720	.17
B 169721	.47
B 169722	.12
B 169723	.02
B 169724	.04
B 169725	1.77
RE B 169725	1.77
RRE B 169725	1.86
B 169726	.47
B 169727	.70
B 169728	.37
B 169729	.21
B 169730	.65
STANDARD AU-1	3.56

Sample type: SOIL. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

Re assay

All results are considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

Data FA

ACME LYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. NCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(60 53-1716
(9002 Accredited Co.)

ASSAY CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A000960

305 - 455 Granville St., Vancouver BC V6C 1T1

SAMPLE#	Au** gm/mt
B 169701	3.35
B 169702	2.55
B 169703	2.14
B 169704	.23
B 169705	11.90
B 169706	29.64
B 169707	45.85
B 169708	34.19
B 169709	39.75
B 169710	13.78
B 169711	6.36
B 169712	.19
B 169713	30.02
B 169714	10.20
B 169715	.84
B 169716	25.18
RE B 169716	24.83
RRE B 169716	26.33
B 169717	.97
B 169718	.20
B 169719	.08
STANDARD AU-1	3.27

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAR 29 2000 DATE REPORT MAILED: April 4/2000 SIGNED BY. C. D. TOYE, C.L[illegible]G, J. WANG; CERTIFIED B.C. ASSAYERS

All result[illegible] e considered the confidential property of the client. Acme assumes [illegible] liabilities for actual cost of the analysis only.

FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A000960

305 - 455 Granville St., Vancouver BC V6C 1T1

SAMPLE#	Au** gm/mt
B 169701	3.35
B 169702	2.55
B 169703	2.14
B 169704	.23
B 169705	11.90
B 169706	29.64
B 169707	45.85
B 169708	34.19
B 169709	39.75
B 169710	13.78
B 169711	6.36
B 169712	.19
B 169713	30.02
B 169714	10.20
B 169715	.84
B 169716	25.18
RE B 169716	24.83
RRE B 169716	26.33
B 169717	.97
B 169718	.20
B 169719	.08
STANDARD AU-1	3.27

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAR 29 2000 DATE REPORT MAILED: April 4/2000 SIGNED BY. C. Leong D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All resul e considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only. Da FA

005

INTERNATIONAL WAYSIDE

05/10/00 WED 08:18 FAX 6046693041

ALS Chemex
Aurora Laboratory Services Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 Brooksbank Ave., North Vancouver
British Columbia, Canada V7J 2C1
PHONE: 604-984-0221 FAX: 604-984-0218

To: STANDARD DRILLING & ENGINEERING L[illegible] ##

305 - 455 GRANVILLE ST.
VANCOUVER, BC
V6C 1T1

Project : CARIBOO GOLD 2000
Comments: ATTN: FRANK CALLAHAN

Page Number : 1
Total Pages : 1
Certificate Date: 03-MAY-2000
Invoice No. : 100165[illegible]
P.O. Number :
Account : KPS

Replicates BC2K-12

CERTIFICATE OF ANALYSIS A0016535

SAMPLE	PREP CODE		Au FA g/t
169701	208	234	3.25
169702	208	234	2.65
169703	208	234	2.14
169704	208	234	0.24
169705	208	234	12.59
169706	208	234	30.82
169707	208	234	47.81
169708	208	234	35.56
169709	208	234	42.74
169710	208	234	13.90
169711	208	234	6.37
169712	208	234	0.26
169713	208	234	31.30
169714	208	234	8.33
169715	208	234	0.74
169716	208	234	25.68
169717	208	234	1.46
169718	208	234	0.20
169719	208	234	< 0.07

BC2K-12

CERTIFICATION: [signature]

05/10/00 WED 08:18 FAX 8046693041 INTERNATIONAL WAYSIDE 004

ALS Chemex
Aurora Laboratory Services Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 Brooksbank Ave., North Vancouver
British Columbia, Canada V7J 2C1
PHONE: 604-984-0221 FAX: 604-984-0218

To: STANDARD DRILLING & ENGINEERING LTD. ##
305 - 455 GRANVILLE ST.
VANCOUVER, BC
V6C 1T1

Project : CARIBOO GOLD 2000
Comments: ATTN: FRANK CALLAHAN

Page Number :1
Total Pages :1
Certificate Date: 03-MAY-2000
Invoice No. : I0016535
P.O. Number :
Account :KPS

CERTIFICATE OF ANALYSIS A0016535

SAMPLE	PREP CODE		Au FA g/t
169701	208	234	3.25
169702	208	234	2.65
169703	208	234	2.14
169704	208	234	0.24
169705	208	234	12.59
169706	208	234	30.82
169707	208	234	47.81
169708	208	234	35.56
169709	208	234	42.74
169710	208	234	13.90
169711	208	234	6.37
169712	208	234	0.26
169713	208	234	31.30
169714	208	234	8.33
169715	208	234	0.74
169716	208	234	25.68
169717	208	234	1.46
169718	208	234	0.20
169719	208	234	< 0.07

CERTIFICATION: Lawrence Ng

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A001077 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Au** gm/mt
B 169401	.18
B 169402	.03
B 169403	.12
B 169404	.11
B 169405	.36
B 169406	.04
B 169407	.07
B 169408	2.13
B 169409	.02
B 169410	.02
RE B 169410	.02
RRE B 169410	.02
B 169411	<.01
B 169412	.02
B 169413	.02
B 169414	.02
B 169415	<.01
B 169416	<.01
B 169417	.33
B 169418	.21
B 169419	11.12
B 169420	12.23
B 169421	1.85
B 169422	8.56
RE B 169422	9.05
RRE B 169422	8.79
B 169423	5.14
B 169424	4.68
B 169425	.29
B 169426	1.13
B 169427	17.61
B 169428	34.32
B 169429	36.63
B 169430	16.19
STANDARD AU-1	3.22

GROUP 3 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE. ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: APR 6 2000 DATE REPORT MAILED: April 13/2000 SIGNED BY: ..... D. TOYE, C.LEONG, J. WANG: CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

SAMPLE#	Au** gm/mt
B 169431	2.06
B 169432	6.71
B 169433	4.19
B 169434	12.84
B 169435	39.89
B 169436	25.20
B 169437	2.60
B 169438	9.68
B 169439	.42
B 169440	3.50
B 169441	3.00
B 169442	8.70
RE B 169442	8.71
RRE B 169442	8.70
B 169443	3.72
B 169444	2.32
B 169445	.56
B 169446	.45
B 169447	.11
B 169448	.14
B 169449	.20
B 169450	.11
B 169451	.11
B 169452	.06
B 169453	.04
B 169454	.03
RE B 169454	.05
RRE B 169454	.03
B 169455	.03
B 169456	.02
B 169457	.02
B 169458	.19
B 169459	.03
B 169460	.01
B 169461	<.01
STANDARD AU-1	3.23

Sample type: CORE. Samples beginning 'RE' are reruns and 'RRE' are reject reruns.

All results are considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

SAMPLE#	Au** gm/mt
B 169462	<.01
B 169463	<.01
B 169464	<.01
B 169465	<.01
B 169466	<.01
B 169467	<.01
B 169468	<.01
B 169469	.02
RE B 169469	.02
RRE B 169469	.01
B 169470	.03
B 169471	.02
B 169472	.05
B 169473	.04
B 169474	.16
STANDARD AU-1	3.28

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Standard Drilling File # A001248 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: R. Hall

SAMPLE#	Au** gm/mt
B 169901	.04
B 169902	.01
B 169903	<.01
B 169904	.02
B 169905	<.01
B 169906	.01
B 169907	.16
B 169908	<.01
B 169909	<.01
B 169910	<.01
RE B 169910	<.01
RRE B 169910	<.01
B 169911	<.01
B 169912	.02
B 169913	.02
B 169914	<.01
B 169915	<.01
B 169916	<.01
B 169917	<.01
B 169918	.02
B 169919	.01
B 169920	<.01
B 169921	.01
B 169922	<.01
RE B 169922	<.01
RRE B 169922	<.01
B 169923	.39
B 169924	1.69
B 169925	.06
B 169926	.03
B 169927	.22
B 169928	.39
B 169929	.62
B 169930	.10
STANDARD AU-1	3.33

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: APR 24 2000 DATE REPORT MAILED: April 27/2000 SIGNED BY..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All ts are considered the confidential property of the client. Acme assu liabilities for actual cost of the analysis only. FA

SAMPLE#	Au** gm/mt
B 169931	.53
B 169932	.29
B 169933	.49
B 169934	.07
B 169935	7.72
B 169936	3.59
B 169937	.03
B 169938	.86
B 169939	2.23
B 169940	2.26
B 169941	4.07
B 169942	3.36
RE B 169942	3.31
RRE B 169942	3.26
B 169943	1.55
B 169944	.81
B 169945	.04
B 169946	.25
B 169947	.26
B 169948	.07
B 169949	4.28
B 169950	.70
B 169951	.31
B 169952	3.82
B 169953	4.56
B 169954	.03
RE B 169954	.03
RRE B 169954	.03
B 169955	.54
B 169956	2.41
B 169957	.23
B 169958	.30
B 169959	.47
B 169960	.60
B 169961	.11
STANDARD AU-1	3.37

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis to

SAMPLE#	Au** gm/mt
B 169962	.04
B 169963	.14
B 169964	.09
B 169965	.09
RE B 169965	.08

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

FA

ACME ANALYTICAL LABORATORIES LTD. (ISO 9002 Accredited Co.) 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716

ASSAY CERTIFICATE

Standard Drilling PROTECT CARIBOO GOLD File # A001465 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Rose

SAMPLE#	Au** gm/mt
B 169966	.06
B 169967	.79
B 169968	.13
B 169969	31.12
B 169970	1.48
B 169971	5.08
B 169972	.48
B 169973	.11
B 169974	.06
B 169975	.04
B 169976	.19
RE B 169976	.22
RRE B 169976	.19
B 169977	.08
B 169978	.08
B 169979	.62
B 169980	.34
B 169981	1.09
B 169982	.40
B 169983	.04
B 169984	.05
B 169985	.03
B 169986	.28
B 169987	.79
B 169988	.78
RE B 169988	.76
RRE B 169988	.75
B 169989	.42
B 169990	.03
B 169991	.03
B 169992	<.01
B 169993	<.01
B 169994	.05
B 169995	1.05
STANDARD AU-1	3.47

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAY 15 2000 DATE REPORT MAILED: May 18/2000 SIGNED BY ..D. TOYE, C.LEONG J. WANG; CERTIFIED B.C. ASSAYERS

All results considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

DF/FA

SAMPLE#	Au** gm/mt
B 169996	.02
B 169997	<.01
B 169998	<.01
B 169999	<.01
B 170000	<.01
B 172028	<.01
B 172029	<.01
B 172030	<.01
RE B 172030	<.01
RRE B 172030	<.01
B 172031	<.01
B 172032	<.01
B 172033	<.01
STANDARD AU-1	3.47

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604) 253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD File # A001361

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** gm/mt
B 172001	<.01
B 172002	<.01
B 172003	<.01
B 172004	<.01
B 172005	<.01
B 172006	<.01
B 172007	<.01
B 172008	<.01
B 172009	<.01
B 172010	.02
RE B 172010	.02
RRE B 172010	.02
B 172011	.05
B 172012	.01
B 172013	<.01
B 172014	<.01
B 172015	<.01
B 172016	<.01
B 172017	<.01
B 172018	<.01
B 172019	.08
B 172020	.34
B 172021	.08
B 172022	.20
RE B 172022	.21
RRE B 172022	.21
B 172023	.26
B 172024	.23
B 172025	.04
B 172026	14.17
B 172027	.12
STANDARD AU-1	3.38

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns

DATE RECEIVED: MAY 3 2000 DATE REPORT MAILED: May 5/2000 SIGNED BY. ..... D. TOYE, C. LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

DF/FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604) 253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A001846 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** gm/mt
0001	.07
0002	.04
0003	.10
0004	.63
0005	.11
0006	.10
0007	.01
0008	.01
0009	<.01
0010	<.01
RE 0010	<.01
RRE 0010	.01
0011	.13
0012	.03
0013	.10
0014	.15
0015	.23
0016	.02
0017	.02
0018	.01
0019	.01
0020	<.01
0021	<.01
0022	<.01
RE 0022	<.01
RRE 0022	<.01
0023	<.01
0024	<.01
0025	<.01
0026	.04
0027	.13
0028	<.01
0029	<.01
0030	<.01
STANDARD AU-1	3.57

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUN 14 2000 DATE REPORT MAILED: Jun 20/00 SIGNED BY ..D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** gm/mt
0031	<.01
0032	.02
0033	<.01
0034	<.01
0035	<.01
0036	.01
0037	<.01
0038	<.01
0039	.02
0040	<.01
0041	<.01
0042	<.01
RE 0042	.01
RRE 0042	<.01
0043	<.01
0044	<.01
0045	<.01
0046	<.01
0047	<.01
0048	<.01
0049	<.01
0050	<.01
0051	<.01
0052	<.01
0053	<.01
0054	<.01
RE 0054	<.01
RRE 0054	<.01
0055	<.01
0056	<.01
0057	<.01
0058	<.01
0059	<.01
0060	<.01
0061	<.01
STANDARD AU-1	3.51

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** gm/mt
0062	<.01
0063	<.01
0064	.01
0065	<.01
0066	<.01
0067	<.01
0068	<.01
0069	.01
0070	<.01
0071	<.01
0072	<.01
RE 0072	<.01
RRE 0072	<.01
0073	<.01
0074	<.01
0075	<.01
0076	<.01
0077	<.01
0078	.01
0079	<.01
0080	.01
0081	<.01
0082	<.01
0083	<.01
0084	<.01
RE 0084	.01
RRE 0084	<.01
0085	<.01
0086	<.01
0087	<.01
0088	<.01
STANDARD AU-1	3.70

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. (ISO 9002 Accredited Co.)
852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716

ASSAY CERTIFICATE

Standard Drilling PROJECT: CARIBOO GOLD File # A000166R

305 - 455 Granville St. Vancouver BC V6C 1T1 Submitted by: K. Dodd

SAMPLE#	Au** gm/mt
B 172034	.02
B 172035	.06
B 172036	.02
B 172037	<.01
B 172038	<.01
B 172039	<.01
B 172040	<.01
B 172041	<.01
B 172042	<.01
B 172043	<.01
B 172044	<.01
B 172045	<.01
RE B 172045	<.01
RRE B 172045	<.01
B 172046	<.01
B 172047	<.01
B 172048	<.01
B 172049	<.01
B 172050	<.01
B 172051	<.01
STANDARD AU-1	3.60

BC2K-17 core

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAY 31 2000 DATE REPORT MAILED: June 2/00 SIGNED BY: C. Leong, D. TOYE, C. LEONG, J. [illegible] CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ___

ASSAY CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD File # A001602 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** gm/mt
0089	<.01
0090	.01
0091	.85
0092	<.01
0093	.08
0094	.02
0095	.03
0096	.03
0097	.52
0098	<.01
RE 0098	<.01
RRE 0098	.01
0099	.63
0100	.90
0101	.81
0102	.79
0103	.23
0104	.03
0105	.74
0106	<.01
0107	.12
0108	1.72
0109	.06
0110	.06
RE 0110	.06
RRE 0110	.07
0111	.21
0112	.03
0113	.06
0114	<.01
0115	<.01
0116	<.01
0117	<.01
0118	<.01
STANDARD AU-1	3.63

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAY 25 2000 DATE REPORT MAILED: May 30/2000 SIGNED BY: C. Leong .D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

SAMPLE#	Au** gm/mt
0119	.02
0120	.03
0121	.03
0122	.05
0123	.02
0214	.01
0215	.01
RE 0215	<.01
RRE 0215	.01
0216	.03
0217	.08
0218	.03
0219	.02
STANDARD AU-1	3.61

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

ACME ANALYTICAL LABORATORIES LTD. (ISO 9002 Accredited)
852 E. Hastings St., Vancouver, BC V6A 1R6 PHONE (604) 253-3158 FAX (604) 253-1716

ASSAY CERTIFICATE

Bard Drilling PROJECT CARIBOO GOLD File # A001626 Page 1

505 - 625 Granville St., Vancouver, BC V6C 1X8 Submitted by: B. Hall

BCZK-18 core.

SAMPLE#	Au** gm/mt
0124	.02
0125	.13
0126	.06
0127	.01
0128	.04
0129	.25
0130	.02
0131	.02
0132	.06
0133	.02
0134	.10
RE 0134	.09
RRE 0134	.12
0135	.08
0136	.07
0137	.03
0138	.31
0139	.02
0140	.12
0141	<.01
0142	<.01
0143	.07
0144	<.01
0145	.02
0146	1.08
RE 0146	1.05
RRE 0146	1.18
0147	.02
0148	.10
0149	<.01
0150	.01
0151	<.01
0152	<.01
0153	.27
STANDARD AU-1	3.62

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAY 29 20 DATE REPORT MAILED: Jun 1/00 SIGNED BY. C. Leong D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYER

All results are considered the ...ential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** gm/mt
0154	.01
0155	<.01
0156	<.01
0157	.02
0158	.02
0159	.02
0160	.02
0161	<.01
0162	<.01
0163	<.01
0164	.03
0165	<.01
RE 0165	<.01
RRE 0165	<.01
0166	<.01
0167	.02
0168	.09
0169	<.01
0170	<.01
0171	.03
0172	.26
0173	.16
0174	.16
0175	.06
0176	1.49
0177	.04
0178	.03
RE 0178	.02
RRE 0178	.02
0179	.01
0180	.02
0181	<.01
0182	<.01
0183	<.01
0184	<.01
STANDARD AU-1	3.58

Sample typ ...ORE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the ...ential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data L FA

JUN 1'00 15:58 FR ACME LABS 604 253 1716 TO 12509943338 P.04/05

SAMPLE#	Au** gm/mt
0185	.01
0186	<.01
0187	<.01
0188	.02
0189	.02
0190	.02
0191	<.01
0192	<.01
0193	.02
0194	<.01
RE 0194	<.01
RRE 0194	.01
0195	.02
0196	.02
0197	<.01
0198	<.01
0199	.01
0200	.01
0201	<.01
0202	.02
0203	<.01
0204	.04
0205	.04
0206	.04
RE 0206	.03
RRE 0206	.03
0207	<.01
0208	.05
0209	.13
0210	.07
0211	<.01
0212	<.01
0213	<.01
0220	.02
0221	.04
STANDARD AU-1	3.50

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Date ___ FA ___

** TOTAL PAGE.005 **

604 253 1716 (2 .0009943038 P.03/05

JUN 1'2: 15:58 FR ACME LABS

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604) 253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

International Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD 2K File # A0[illegible]761 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** gm/mt	Au2 gm/mt
0222	.02	-
0223	.04	-
0224	1.52	-
0225	41.17	43.56
0226	14.91	15.45
0227	12.45	14.66
0228	2.32	-
0229	19.25	18.36
0230	36.98	39.62
0231	15.51	15.92
0232	41.47	42.23
RE 0232	41.98	-
RRE 0232	41.87	-
0233	30.11	29.93
0234	12.36	11.58
0235	3.04	-
0236	21.28	19.52
0237	5.17	-
0238	.05	-
0239	.02	-
0240	<.01	-
0241	.03	-
0242	.08	-
0243	.04	-
0244	.03	-
RE 0244	.03	-
RRE 0244	.05	-
0245	6.96	-
0246	.05	-
0247	1.35	-
0248	.03	-
0249	.87	-
0250	.06	-
0251	.03	-
STANDARD AU-1	3.63	-

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
AU2 BY FIRE ASSAY BY GRAVIMETRIC FINISHED.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

(Second column is gravimetric finish.)

DATE RECEIVED: JUN 8 2000 DATE REPORT MAILED: Jun 15/00 SIGNED BY. . . . . D. TOYE, C. LEUNG, [illegible]ANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis o[illegible]

Data f FA f

SAMPLE#	Au** gm/mt
0252	1.24
0253	.42
0254	.55
0255	.03
0256	<.01
0257	.03
0258	.02
0259	.01
0260	.01
RE 0260	.01
RRE 0260	<.01
0261	<.01
0262	<.01
0263	.02
0264	<.01
0265	<.01
STANDARD AU-1	3.60

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604) 253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD 2000 File # A00187

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** gm/mt
0266	<.01
0267	.01
0268	.08
0269	1.03
0270	<.01
0271	.07
0272	.29
0273	<.01
0274	2.43
0275	1.64
0276	.14
RE 0276	.16
RRE 0276	.48
0277	.13
0278	.56
0279	.59
0280	.31
0281	.28
0282	.53
0283	.11
0284	1.94
0285	.07
0286	.03
0287	.11
0288	1.06
RE 0288	1.00
RRE 0288	1.00
0289	1.48
0290	.69
0291	.26
0292	3.47
0293	1.27
0294	.11
0295	4.22
STANDARD AU-1	3.63

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUN 16 2000 DATE REPORT MAILED: Jun 23/00 SIGNED BY. J. Wang .D. TOYE, C.L. ONG, ANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis

Data FA

SAMPLE#	Au** gm/mt
0296	.08
0297	.37
0298	7.98
0299	.01
0300	.02
0301	<.01
0302	<.01
0303	<.01
0304	<.01
RE 0304	<.01
RRE 0304	<.01
0305	<.01
0306	<.01
0307	<.01
0308	.08
STANDARD AU-1	3.76

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604) 3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD 2000 File # A00197

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** gm/mt
0309	.27
0310	.15
0311	.18
0312	.22
0313	.55
0314	.54
0315	.11
0316	.16
0317	.40
0318	.24
0319	.10
0320	.02
RE 0320	.01
RRE 0320	.02
0321	.02
0322	<.01
0323	<.01
0324	.03
0325	.02
0326	<.01
0327	.03
0328	.03
0329	.03
0330	.01
0331	.01
0332	.01
RE 0332	<.01
RRE 0332	<.01
0333	<.01
0334	<.01
0335	<.01
0336	<.01
0337	.01
0338	.01
STANDARD AU-1	3.63

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUN 23 2000 DATE REPORT MAILED: July 4/00 SIGNED BY ..... D. TOYE, C.L... ...ANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analys...

Data FA

SAMPLE#	Au** gm/mt
0339	.02
0340	.04
0341	1.25
RE 0341	1.19

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' ar[illegible] Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analy[illegible]

Data [illegible] FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604) -3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A001913 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** gm/mt
0351	.97
0352	.07
0353	.09
0354	.27
0355	1.53
0356	1.07
0357	1.16
0358	1.01
0359	.26
0360	.09
RE 0360	.10
RRE 0360	.10
0361	.02
0362	.03
0363	.05
0364	.02
0365	.02
0366	.01
0367	<.01
0368	<.01
0369	.06
0370	.14
0371	<.01
0372	<.01
RE 0372	<.01
RRE 0372	<.01
0373	<.01
0374	<.01
0375	<.01
0376	<.01
0377	<.01
0378	<.01
0379	<.01
0380	<.01
STANDARD AU-1	3.46

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUN 20 2000 DATE REPORT MAILED: Jun 29/00 SIGNED BY ..D. TOYE, C.LEONG ; WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** gm/mt
0381	<.01
0382	<.01
0383	<.01
0384	<.01
0385	<.01
0386	<.01
0387	.01
0388	.01
RE 0388	<.01
RRE 0388	.01
0389	.01
0390	.01
STANDARD AU-1	3.58

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002215 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** gm/mt
0391	2.21
0392	2.14
0393	2.64
0394	.09
0395	8.87
0396	.24
0397	.03
0398	<.01
0399	<.01
0400	.06
RE 0400	.06
RRE 0400	.06
0401	.13
0402	.05
0403	.02
0404	.03
0405	.05
0406	.04
0408	.03
0409	.05
0410	.02
0411	<.01
0412	.26
RE 0412	.28
RRE 0412	.26
0413	3.99
0414	1.48
0415	3.14
0416	.93
0417	.30
0418	.55
0419	1.36
0420	1.39
0421	1.77
STANDARD AU-1	3.51

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUL 10 2000 DATE REPORT MAILED: July 18/00 SIGNED BY. . . . . D. TOYE, C. LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** gm/mt
0422	.19
0423	6.95
0424	.92
0425	.08
0426	.11
0427	.17
0428	.07
0429	.03
0430	.02
RE 0430	.04
RRE 0430	.02
0431	2.00
0432	1.16
0433	.05
0434	.03
0435	<.01
0436	<.01
0437	<.01
0438	<.01
0439	<.01
0440	<.01
0441	<.01
0442	.26
RE 0442	.24
RRE 0442	.22
0443	<.01
0444	<.01
0445	.11
0446	<.01
0447	<.01
STANDARD AU-1	3.55

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002493 Page 1
305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** gm/mt
0493	.18
0494	.06
0495	.07
0496	.13
0497	.09
0498	.17
0499	.24
0500	<.01
0501	.88
0502	.58
RE 0502	.59
RRE 0502	.59
0503	<.01
0504	.02
0505	.37
0506	.09
0507	.09
0508	.11
0509	.05
0510	.03
0613	.22
0614	<.01
0615	.06
0616	.03
RE 0616	.03
RRE 0616	.02
0617	.39
0618	.21
0619	.04
0620	.19
0621	.21
0622	.10
0623	1.80
0624	.22
STANDARD AU-1	3.51

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUL 21 2000 DATE REPORT MAILED: Aug 3/00 SIGNED BY: D. TOYE, C. LONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** gm/mt
0625	.85
0626	.97
0627	.90
0628	1.76
0629	.10
0630	.30
RE 0630	.33
RRE 0630	.30
0631	5.74
0632	1.69
0633	1.60
0634	.01
STANDARD AU-1	3.52

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. (ISO 9002 Accredited Co.) 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002438 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** gm/mt
0452	.08
0453	.10
0454	.42
0455	.03
0456	2.09
0457	.26
0458	.18
0459	.05
0460	<.01
0461	.05
0462	.12
RE 0462	.12
RRE 0462	.13
0463	3.05
0464	1.50
0465	1.92
0466	4.59
0467	.10
0468	.38
0469	.01
0470	.03
0471	.58
0472	.05
0473	.04
0474	.04
RE 0474	.05
RRE 0474	.04
0475	.04
0476	.01
0477	.18
0478	.41
0479	.32
0480	.13
0481	.50
STANDARD AU-1	3.50

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUL 19 2000 DATE REPORT MAILED: July 28/00 SIGNED BY: D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** gm/mt
0482	.33
0483	.09
0484	.16
0485	2.87
0486	.15
0487	.04
0488	.04
RE 0488	.04
RRE 0488	.06
0489	.07
0490	.09
0491	1.86
0492	.07

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002641 Page 1
305 - 455 Granville St., Vancouver BC V6C 1T1

SAMPLE#	Au** gm/mt
0511	.16
0512	.10
0513	.42
0514	.03
0515	.07
0516	.05
0517	.15
0518	8.41
0519	8.02
0520	.04
RE 0520	.04
RRE 0520	.05
0521	.11
0522	<.01
0523	6.14
0524	.01
0525	.04
0526	.04
0527	.01
0528	<.01
0529	<.01
0530	.01
0531	.01
0532	.01
0533	.01
0534	<.01
RE 0534	<.01
RRE 0534	<.01
0535	.02
0536	.01
0537	<.01
0538	.05
0539	.07
0540	.03
STANDARD AU-1	3.51

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUL 28 2000 DATE REPORT MAILED: Aug 4/00 SIGNED BY. C. D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** gm/mt
0541	.01
0542	3.57
0543	4.67
0544	1.54
0545	2.11
0546	9.29
0547	1.83
0548	1.38
0549	.60
0550	1.96
RE 0550	1.94
RRE 0550	2.11
0601	.08
0602	.39
0603	.08
0604	34.03
0605	31.05
0606	3.34
0607	16.62
0608	5.38
0609	.84
0610	6.55
0611	.06
0612	.04
STANDARD AU-1	3.57

Sample type: CORE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002724 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: R. Hall

SAMPLE#	Au** gm/mt
0551	.16
0552	.09
0553	.48
0554	.24
0555	.03
0556	.07
0557	14.13
0558	.33
0559	.06
0560	.13
RE 0560	.16
RRE 0560	.19
0561	.32
0562	3.83
0563	.07
0564	.03
0565	.02
0566	.06
0567	<.01
0568	<.01
0569	<.01
0570	.02
0571	.02
0572	.15
RE 0572	.14
RRE 0572	.16
0573	.08
0574	.55
0575	<.01
0576	1.85
0577	7.55
0578	1.42
0579	.19
0580	.11
STANDARD AU-1	3.66

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: AUG 2 2000 DATE REPORT MAILED: Aug 10/00 SIGNED BY: D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** gm/mt
0581	.31
0582	.29
0583	.05
0584	.06
0585	.30
0586	1.12
0587	1.08
0588	.07
RE 0588	.07
RRE 0588	.06
0589	<.01
0590	<.01
0591	<.01
0592	.03
STANDARD AU-1	3.57

Sample type: CORE R150 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. File # A002860 Page
305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** gm/mt	Au** gm/mt
0651	.05	-
0652	1.29	-
0653	.03	-
0654	.06	-
0655	.08	-
0656	.54	-
0657	.01	-
0658	.03	-
0659	.03	-
0660	.02	-
RE 0660	.01	-
RRE 0660	.02	-
0661	<.01	-
0662	.04	-
0663	<.01	-
0664	<.01	-
0665	.03	-
0666	.02	-
0667	<.01	-
0668	.03	-
0669	.09	-
0670	<.01	-
0671	.02	-
0672	<.01	-
RE 0672	<.01	-
RRE 0672	<.01	-
0673	5.46	-
0674	.91	-
0675	20.05	20.81
0676	.19	-
0677	.04	-
0678	.47	-
0679	20.84	21.59
0680	.36	-
STANDARD AU-1	3.57	-

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: AUG 9 2000 DATE REPORT MAILED: Aug 15/00 SIGNED BY. C. Leong D. TOYE, C. LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data___ FA___

SAMPLE#	Au** gm/mt	Au** gm/mt
0681	.19	-
0682	14.42	14.77
0683	.22	-
0684	2.44	2.83
0685	23.83	24.54
0686	53.36	55.76
0687	42.32	43.99
0688	25.09	26.37
0689	51.84	51.49
0690	2.76	2.95
0691	4.92	5.18
0692	.40	-
RE 0692	.42	-
RRE 0692	.41	-
0693	.40	-
0694	.21	-
0695	<.01	-
0696	7.18	7.13
0697	.01	-
0698	.03	-
0699	.01	-
0700	.08	-
0701	.46	-
0702	.03	-
0703	.01	-
0704	<.01	-
RE 0704	.02	-
RRE 0704	.02	-
0705	.13	-
0706	.02	-
0707	.03	-
0708	<.01	-
0709	<.01	-
0710	<.01	-
0711	.02	-
STANDARD AU-1	3.50	-

Sample type: CORE R150 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ___

SAMPLE#	Au** gm/mt
0712	.04
0713	.07
0714	.01
0715	.02
0716	.03
0717	.03
0718	5.47
0719	.01
0720	.04
0721	.06
0722	.02
RE 0722	<.01
RRE 0722	<.01
0723	.01
0724	.03
0725	<.01
0726	<.01
0727	.02
0728	.05
STANDARD AU-1	3.50

Sample type: CORE R150 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604) 253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A00030[illegible]

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** gm/mt
0751	.01
0752	.01
0753	.01
0754	.14
0755	.16
0756	.12
0757	.08
0758	.11
0759	23.49
0760	13.04
0761	3.81
0762	1.20
RE 0762	1.22
RRE 0762	1.28
0763	9.41
0764	1.75
0765	17.94
0766	4.38
0767	.16
0768	.19
0769	.10
0770	.08
0771	.06
0772	.50
0773	.09
0774	1.05
RE 0774	1.16
RRE 0774	1.15
0775	.16
0776	.02
0777	.01
0778	.37
0779	1.34
0780	1.28
STANDARD AU-1	3.59

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: AUG 15 2000 DATE REPORT MAILED: Aug 22/00 SIGNED BY. C. [illegible] D. TOYE, C. [illegible] J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analy[illegible]niy.

Data ___ FA ___

SAMPLE#	Au** gm/mt
0781	2.03
0782	.81
0783	2.60
0784	.28
0785	.67
0786	.67
0787	2.21
0788	2.32
0789	7.04
0790	6.86
RE 0790	6.87
RRE 0790	6.79
0791	6.30
0792	2.69
0793	9.50
0794	1.46
0795	13.97
0796	27.83
0797	2.25
0798	3.90
0799	1.62
0800	.19
0801	3.65
0802	.35
RE 0802	.39
RRE 0802	.38
0803	.04
0804	.02
0805	.03
0806	.16
0807	.80
0808	.20
0809	.09
0810	.03
0811	.03
STANDARD AU-1	3.64

Sample type: CORE R150 60C. Samples beginning 'RE' are Returns and 'RRE' are Reject Returns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** gm/mt
0812	<.01
0813	.01
0814	<.01
0815	6.37
RE 0815	5.85
STANDARD AU-1	3.51

Sample type: CORE R150 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003184 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ken Lord

SAMPLE#	Au** gm/mt
0816	2.34
0817	.07
0818	2.32
0819	5.77
0820	16.62
0821	40.15
0822	20.43
0823	10.02
0824	6.87
0825	2.29
0826	5.65
RE 0826	5.56
RRE 0826	5.31
0827	2.41
0828	23.10
0829	.24
0830	6.38
0831	10.45
0832	2.56
0833	1.05
0834	.06
0835	.06
0836	.03
0837	.01
0838	.02
RE 0838	.01
RRE 0838	.01
0839	8.33
0840	<.01
0841	.01
0842	<.01
0843	.03
0844	.43
0845	.21
STANDARD AU-1	3.53

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: AUG 23 2000 DATE REPORT MAILED: Sept 1/00 SIGNED BY. D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** gm/mt
0846	2.85
0847	.94
0848	3.06
0849	.08
0850	.06
0901	.04
0902	.02
RE 0902	<.01
RRE 0902	<.01
0903	<.01
0904	<.01
0905	<.01
0906	.01
STANDARD AU-1	3.66

Sample type: CORE R150 60C. Samples beginning 'RE' are R uns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003051 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: R. Hall

SAMPLE#	Au** gm/mt	Au** gm/mt
0729	.05	-
0730	3.84	-
0731	8.92	-
0732	.07	-
0733	2.53	-
0734	6.51	-
0735	4.11	-
0736	23.22	-
0737	22.88	-
0738	.11	-
RE 0738	.08	-
RRE 0738	.09	-
0739	.08	-
0740	.02	-
0741	.02	-
0742	<.01	-
0743	.01	-
0744	<.01	-
0745	<.01	-
0746	<.01	-
0747	.02	-
0851	.35	-
0852	.07	.11
RE 0852	.09	.07
RRE 0852	.43	.16
0853	.05	-
0854	.08	-
0855	.57	-
0856	3.94	-
0857	.60	-
0858	8.11	-
0859	3.19	-
0860	2.31	-
0861	.82	-
STANDARD AU-1	3.61	-

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: AUG 17 2000 DATE REPORT MAILED: Aug 25/00 SIGNED BY..... C. Leong .D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data FA

SAMPLE#	Au** gm/mt
0862	1.22
0863	.13
0864	.31
0865	.08
0866	.02
0867	.01
0868	.28
0869	.01
0870	.03
0871	.05
0872	7.38
RE 0873	.13
0873	.08
0874	.01
0875	.07
0876	5.05
0877	20.42
0878	8.71
0879	4.12
0880	4.02
0881	.03
0882	7.43
0883	5.43
0884	8.13
RE 0884	8.25
RRE 0884	9.51
0885	58.85
0886	16.23
0887	9.17
0888	5.79
0889	32.63
0890	5.72
0891	10.42
0892	13.59
STANDARD AU-1	3.55

Sample type: CORE R150 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** gm/mt
0893	11.25
0894	4.68
0895	3.49
0896	.25
0897	46.44
0898	3.26
RE 0898	3.28
RRE 0898	3.21
0899	16.00
0900	.04

Sample type: CORE R150 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data__ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003830

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: K. Ross

SAMPLE#	Au** gm/mt
1601	<.01
1602	<.01
1603	.02
1604	.02
1605	<.01
1606	<.01
1607	<.01
1608	<.01
1609	.01
1610	<.01
1611	<.01
1612	<.01
RE 1612	<.01
RRE 1612	<.01
1613	<.01
1614	<.01
1615	<.01
1616	<.01
1617	<.01
1618	<.01
STANDARD AU-1	3.72

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: SEP 28 2000 DATE REPORT MAILED: Oct 4/00 SIGNED BY. C.T. D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data F FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003139

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ken Lord

SAMPLE#	Au** gm/mt
0907	5.45
0908	.07
0909	1.75
0910	.65
0911	.07
0912	.32
0913	1.74
0914	5.15
0915	12.55
0916	12.76
RE 0916	13.40
RRE 0916	14.08
0917	.36
0918	.78
0919	.94
0920	.04
0921	.02
0922	<.01
0923	<.01
0924	<.01
0925	3.87
0926	.01
RE 0926	<.01
RRE 0926	.03
0927	33.66
0928	4.22
0929	9.19
0930	14.03
0931	.99
STANDARD AU-1	3.55

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: AUG 24 2000 DATE REPORT MAILED: Sept 5/00 SIGNED BY. C. T. D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. File # A003473 Page 1
305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** gm/mt	Au** gm/mt
0951	.03	-
0952	.05	-
0953	<.01	-
0954	<.01	-
0955	.02	-
0956	<.01	-
0957	<.01	-
0958	<.01	-
0959	<.01	-
0960	<.01	-
0961	<.01	-
0962	<.01	-
RE 0962	<.01	-
RRE 0962	<.01	-
0963	<.01	-
0964	<.01	-
0965	<.01	-
0966	<.01	-
0967	<.01	-
0968	.01	-
0969	.05	-
0970	<.01	-
0971	.11	-
0972	.01	-
0973	<.01	-
0974	.03	-
RE 0974	<.01	-
RRE 0974	.01	-
0975	.01	-
0976	.01	-
0977	9.21	7.78
0978	.01	-
0979	.09	-
0980	.13	-
STANDARD AU-1	3.63	-

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: SEP 11 2000 DATE REPORT MAILED: Sept 20/00 SIGNED BY ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Au** gm/mt
0981	.20
0982	.13
0983	.19
RE 0983	.16

Sample type: CORE R150 60C. Samples beginning 'RE' are Reruns and 'RR' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST ANCOUVER BC V6A 1R6 PHONE) 253-3158 FAX(6 53-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003 Page 1
305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** gm/mt	Au* gm/m
0932	.05	
0933	.04	
0934	.07	
0935	<.01	
0936	.02	
0937	<.01	
0938	<.01	
0939	<.01	
0940	<.01	
0941	<.01	
0942	<.01	
RE 0942	<.01	
RRE 0942	<.01	
0943	<.01	
0944	<.01	
0945	<.01	
0946	<.01	
0947	<.01	
0948	<.01	
0949	<.01	
0950	<.01	
0984	5.46	4.8
0985	<.01	
0986	<.01	
RE 0986	<.01	
RRE 0986	<.01	
0987	<.01	
0988	<.01	
0989	<.01	
0990	<.01	
0991	<.01	
0992	<.01	
0993	<.01	
0994	<.01	
STANDARD AU-1	3.60	

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, YSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Rerun

DATE RECEIVED: SEP 14 2000 DATE REPORT MAILED: Sept 22/00 SIGNED BY. D. TOYE, C. , J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for a al cost of the anal only.

Data FA

SAMPLE#	Au** gm/mt
0995	.02
0996	<.01
0997	.02
0998	<.01
0999	.01
1000	<.01
RE 1000	<.01
RRE 1000	<.01
1501	.02
1502	<.01
1503	<.01
1504	.01
STANDARD AU-1	3.46

Sample type: CORE R150 60C. Samples beginning 'RE' are R[illegible]runs and 'RR[illegible] are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for a[illegible]ual cost of the anal[illegible]nly.

Data V FA

ACME ALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. ANCOUVER BC V6A 1R6 PHONE( )253-3158 FAX(60 53-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A 624

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** gm/mt
1505	.02
1506	.07
1507	.01
1508	<.01
1509	.40
1510	<.01
1511	.02
1512	.23
1513	<.01
1514	.29
RE 1514	.58
RRE 1514	.48
1515	.06
1516	.03
1517	<.01
1518	<.01
1519	<.01
1520	<.01
1521	<.01
1522	<.01
1523	<.01
1524	.01
1525	<.01
1526	<.01
RE 1526	<.01
RRE 1526	<.01
1527	<.01
1528	.02
1529	.02
1530	<.01
1531	<.01
1532	<.01
1533	<.01
1534	<.01
1535	.01
STANDARD AU-1	3.69

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: SEP 18 2000 DATE REPORT MAILED: Sept 25/00 SIGNED BY. .D. TOYE, C. G, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the anal only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A00[illegible] Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** gm/mt
1536	.11
1537	.03
1538	.04
1539	.14
1540	.02
1541	.21
1542	.08
1543	.01
1544	.64
1545	.52
1546	.01
RE 1546	<.01
RRE 1546	<.01
1547	<.01
1548	<.01
1549	.01
1550	.02
1551	.05
1552	.03
1553	.04
1554	.02
1555	.08
1556	<.01
1557	<.01
1558	<.01
RE 1558	<.01
RRE 1558	<.01
1559	<.01
1560	<.01
1561	<.01
1562	.02
1563	.22
1564	.15
1565	1.05
STANDARD AU-1	3.75

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: SEP 22 2000 DATE REPORT MAILED: Oct 2/00 SIGNED BY. C. [illegible]. TOYE, C. [illegible], J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** gm/mt
1566	1.15
1567	.11
1568	.41
1569	.03

Sample type: CORE R150 60C.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the anal[illegible] only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004066 Page 1

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: K ROSS

SAMPLE#	Au** gm/mt
1570	.40
1571	.87
1572	1.14
1573	.16
1574	.04
1575	.01
RE 1575	.02
RRE 1575	.02
1576	.01
1577	<.01
1578	.03
1579	<.01
1580	<.01
1581	<.01
1582	.02
1583	.01
1584	<.01
1585	.02
1586	<.01
1587	.01
1588	.01
RE 1588	.02
RRE 1588	<.01
1589	<.01
1590	<.01
1591	<.01
1592	.05
1593	.04
1594	.49
1595	.43
1596	2.05
1597	1.38
1598	.07
1599	.05
STANDARD AU-1	3.58

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE. ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE 150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 16 2000 DATE REPORT MAILED: Oct 20/00 SIGNED BY..... D. TOYE, C.L. [illegible], J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data___ FA ___

SAMPLE#	Au** gm/mt
1600	1.14
1651	2.88
1652	5.25
1653	.37
1654	.04
1655	.67
1656	.03
1657	.80
RE 1657	1.11
RRE 1657	.96
1658	.46
1659	.55
1660	.09
1661	.69
1662	.17
1663 PULP	1.80
1664 PULP	6.13
STANDARD AU-1	3.58

Sample type: CORE 150 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ___

ACME (LYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. NCOUVER BC V6A 1R6 PHONE(60 253-3158 FAX(604 53-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A00 03
P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: K. Ross

SAMPLE#	Au** gm/mt
1619	.04
1620	.24
1621	.15
1622	.02
1623	.02
1624	.38
1625	<.01
1626	.03
1627	.01
1628	<.01
1629	<.01
1630	.02
RE 1630	<.01
RRE 1630	<.01
1631	<.01
1632 PULP	1.83
1633 PULP	6.33
1634	.03
1635	<.01
1636	.01
1637	.01
1638	<.01
1639	.05
STANDARD AU-1	3.58

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, AN YSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 17 2000 DATE REPORT MAILED: Oct 20/00 SIGNED BY C.T .D. TOYE, C.L , J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analys ly.

Data k FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604) 253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A0051

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: K. Ross

SAMPLE#	Au** gm/mt
1665	.01
1666	.01
1667	.01
1668	<.01
1669	<.01
1670	<.01
1671	.02
1672	<.01
1673	.01
1674	.02
1675	<.01
1676	.01
RE 1676	.01
RRE 1676	.01
1677	<.01
1678	<.01
1679	.02
1680	<.01
1681	.01
1682	.02
1683 PULP	6.44
1684 PULP	1.76
1685	.02
1686	.06
1687	.09
STANDARD AU-1	3.69

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns

DATE RECEIVED: OCT 19 2000 DATE REPORT MAILED: Oct 26/00 SIGNED BY. ..... D. TOYE, C. ... J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analy... ...ty.

Data ✓ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A0[illegible]4435

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: R. Hall

SAMPLE#	Au** gm/mt
1688	<.01
1689	<.01
1690	<.01
1691	<.01
1692	<.01
RE 1692	<.01
RRE 1692	<.01
1693	<.01
1694	.04
1695	.12
STANDARD AU-1	3.59

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 31 2000 DATE REPORT MAILED: Nov 6/00 SIGNED BY. C. Toye ..D. TOYE, C.[illegible], J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analy[illegible]nly.

Data K FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604) 253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. File # A004754
P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: R. Hall

SAMPLE#	Au** gm/mt
1788	.08
1789	.18
1791	2.84
1792	3.03
1795 PULP	1.68
1796	.66
1797	11.43
1798	1.04
1799	.53
1800	.12
1801	.02
RE 1801	.03
RRE 1801	.03
1805	.02
1806	<.01
1807	<.01
1808	.01
1809	.01
1812	.01
1813	<.01
1814 PULP	6.62
1816	.68
1817	.29
1818	.23
STANDARD AU-1	3.61

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: NOV 27 2000 DATE REPORT MAILED: Dec 4/00 SIGNED BY. C. Toye .D. TOYE, C. [illegible], J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analy[illegible] only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. (ISO 9002 Accredited Co.) 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004[illegible] Page 1

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: T.C. Scott

SAMPLE#	Au** gm/mt
1701	<.01
1702	.13
1703	.20
1704	7.38
1705	1.04
1706	.29
1707	.28
1708	<.01
1709	<.01
1710	.01
RE 1710	.01
RRE 1710	<.01
1711	.14
1712	.04
1713	.03
1714	.14
1715	.19
1716	.16
1717	.04
1718	.06
1719	.09
1720 PULP	1.66
1721 PULP	6.51
1722	.09
RE 1722	.09
RRE 1722	.09
1723	.01
1724	.10
1725	<.01
1726	<.01
1727	<.01
1728	<.01
1729	<.01
1730	<.01
STANDARD AU-1	3.57

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: NOV 2 2000 DATE REPORT MAILED: Nov 10/00 SIGNED BY: C. [illegible] D. TOYE, [illegible]NG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the ana[illegible] only.

Data A FA

SAMPLE#	Au** gm/mt
1731	<.01
1732	.02
1733	<.01
1734	.01
1735	<.01
1736	.01
1737	.02
1738	.01
RE 1738	.01
RRE 1738	.02
1739	.30
1740 PULP	.41
1741 PULP	1.67
1742	<.01
STANDARD AU-1	3.57

Sample type: CORE R150 60C. Samples beginning 'RE' are Reruns and 'RR[illegible]are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the anal[illegible]only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. File # A004745 Page 1
P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: R. Hall

SAMPLE#	Au** gm/mt
1743	.13
1744	.02
1745	.05
1746	.07
1747	.04
1748	<.01
1749	<.01
1750	<.01
1751	.11
1752	<.01
RE 1752	<.01
RRE 1752	<.01
1753	14.01
1754	1.06
1755	.05
1756	1.48
1757	.13
1758	.03
1759	21.10
1760	.85
1761	.34
1762	6.68
RE 1762	6.85
RRE 1762	7.13
1763	15.28
1764 PULP	1.76
1765 PULP	6.87
1766	.35
1767	.50
1768	.59
1769	.06
1770	.02
1771	.02
1772 PULP	1.75
1773 PULP	6.93
STANDARD AU-1	3.69

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: NOV 24 2000 DATE REPORT MAILED: Dec 4/00 SIGNED BY. ..... D. TOYE, C.L. WANG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data FA

SAMPLE#	Au** gm/mt
1774	.04
1775	.04
1776	.01
1777	<.01
1778	.01
1779	<.01
1780	<.01
1781	<.01
1782	.02
RE 1782	<.01
RRE 1782	.02
1783	.01
1784	.04
1785	<.01
1786	<.01
1787	<.01
STANDARD AU-1	3.69

Sample type: CORE R150 60C. Samples beginning 'RE' are Reruns and 'RR' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604) 253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. File # A004801 Page
P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: Ken Lord

SAMPLE#	Au** gm/mt
1824	.09
1825	.21
1826	.62
1827	.08
1828	.05
1829	.02
1830	.05
1831	.01
1832	<.01
1833	.03
1834	.01
RE 1834	.02
RRE 1834	.03
1835	.13
1836	.03
1837	.01
1838	<.01
1839	.03
1840	.04
1841	<.01
1842	<.01
1843	<.01
1844	<.01
1845 PULP	6.41
1846 PULP	1.54
1847	<.01
1848	<.01
RE 1848	<.01
RRE 1848	<.01
1849	<.01
1850	.03
1851	.03
1852	.03
1853	<.01
STANDARD AU-1	3.57

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
SAMPLE TYPE: CORE R150 602
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns

DATE RECEIVED: NOV 30 2000 DATE REPORT MAILED: Dec 8/00 SIGNED BY: C. ... D. TOYE, C.L. ... J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data FA

SAMPLE#	Au** gm/mt
1854	.02
1855	<.01
1856	.10
1857	.02
1858	.02
1859	<.01
1860	<.01
1861	<.01
1862	<.01
1863	<.01
1864	<.01
RE 1864	<.01
RRE 1864	<.01
1865	<.01
1866	.01
1867 PULP	6.26
1868 PULP	1.62
STANDARD AU-1	3.62

Sample type: CORE R150 60C. Samples beginning 'RE' are Re uns and 'RRE re Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for act t cost of the analysi ly.

Data F FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604) 253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. File # A004895
P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: Ken Lord

SAMPLE#	Au** gm/mt
1908	.01
1909	.08
1910	<.01
1911	<.01
1912	<.01
1913	<.01
1914	<.01
1915	.02
1916	<.01
RE 1916	.02
RRE 1916	.01
1917	<.01
1918	.24
1919	.06
1920 PULP	6.48
STANDARD AU-1	3.60

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: DEC 6 2000 DATE REPORT MAILED: Dec 11/00 SIGNED BY: C.L. D. TOYE, C.L. J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604) 253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. File # A004755
P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: Ken Lord

SAMPLE#	Au** gm/mt
1867	.02
1868	.19
1869	.28
1870	2.38
1871	5.31
1872	1.05
1873	.41
1874	.02
1875	.20
1876 PULP	6.68
1877	.03
1878	.46
RE 1878	.25
RRE 1878	.46
1879	.02
1880	.03
1881	.07
1882 PULP	1.74
STANDARD AU-1	3.63

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: NOV 27 2000 DATE REPORT MAILED: Dec 4/00 SIGNED BY ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604) 253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. File # A004823
P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: Ken Lord

SAMPLE#	Au** gm/mt
1883	<.01
1884	<.01
1885	.02
1886	.19
1887	.02
1888	.05
1889	.02
1890	.01
1891	<.01
1892	<.01
RE 1892	<.01
RRE 1892	.01
1893	<.01
1894	.02
1895	.02
1896	<.01
1897	.01
1898	.04
1899	.02
1900	.04
1901	.26
1902	.04
RE 1902	.03
RRE 1902	.03
1903	.25
1904	.02
1905	.03
1906	.03
1907 PULP	6.44
STANDARD AU-1	3.67

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: DEC 1 2000 DATE REPORT MAILED: Dec 8/00 SIGNED BY. C.T. D. TOYE, C.L[illegible], J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

APPENDIX IX

ASSAY CERTIFICATES

PART 2 - DIAMOND DRILL HOLE GEOCHEMISTRY / WHOLE ROCK ASSAY CERTIFICATES

PART 2

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

WHOLE ROCK ICP ANALYSIS

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A001077R4

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	SiO2 %	Al2O3 %	Fe2O3 %	MgO %	CaO %	Na2O %	K2O %	TiO2 %	P2O5 %	MnO %	Cr2O3 %	Ba ppm	Ni ppm	Sr ppm	Zr ppm	Y ppm	Nb ppm	Sc ppm	LOI %	TOT/C %	TOT/S %	SUM %
B 169405	57.43	10.09	6.53	3.56	7.66	.23	2.85	1.26	.19	.13	.009	1052	47	152	124	17	16	14	9.7	3.28	1.57	99.80
B 169408	38.11	11.23	9.17	6.07	13.82	.29	2.66	.86	.21	.17	.045	2622	167	287	56	12	16	25	13.5	5.76	1.37	96.50
B 169411	41.51	15.06	13.01	3.38	8.04	1.33	2.32	2.79	.55	.16	.005	2088	58	267	179	26	38	25	9.6	3.41	4.22	98.06
B 169414	66.97	9.87	6.20	2.77	4.36	.29	2.56	.50	.04	.13	.006	1072	47	177	92	18	<10	10	6.0	2.56	.94	99.86
B 169417	46.55	17.46	12.62	2.20	3.51	.33	4.19	2.39	.41	.05	.024	2648	69	193	145	24	26	26	9.6	1.60	7.13	99.69
B 169420	33.75	23.41	14.74	1.36	2.63	.38	6.58	4.69	.73	.05	.006	4455	48	234	281	42	54	42	10.6	.74	10.17	99.51
B 169423	31.03	23.50	16.49	.86	1.74	.36	6.59	5.56	.74	.02	.006	4859	<20	179	321	49	70	37	12.0	.35	12.35	99.52
B 169428	28.59	21.57	19.46	1.73	3.28	.39	6.05	4.13	.32	.09	.012	2382	<20	215	238	33	44	35	13.6	1.23	13.59	99.56
B 169432	29.02	22.11	15.87	2.92	5.95	.50	5.93	3.94	.40	.17	.039	3047	68	346	222	35	45	42	12.3	2.42	9.19	99.59
B 169436	19.79	15.34	29.39	2.05	4.33	.40	3.79	2.58	.36	.11	.005	2703	<20	283	193	26	38	26	21.2	1.61	23.18	99.72
B 169441	34.80	26.50	15.01	1.26	1.47	.65	6.86	1.25	.30	.04	.014	3618	87	163	346	45	15	23	11.0	.46	10.45	99.65
RE B 169441	34.84	26.41	14.66	1.25	1.47	.63	6.94	1.26	.36	.04	.015	3605	80	163	357	47	19	23	11.3	.48	10.45	99.67
B 169444	42.34	31.84	4.76	1.14	.88	.66	8.61	1.35	.23	.02	.017	4778	39	147	387	53	22	25	7.1	.20	2.77	99.57
B 169446	66.72	10.80	8.30	.94	1.41	.23	2.96	1.11	.21	.04	.008	1386	48	87	106	16	18	15	7.0	1.02	5.86	99.92
B 169449	46.34	20.02	13.12	1.08	1.08	.32	5.42	.80	.14	.03	.006	1583	61	115	199	37	12	16	11.2	.92	9.69	99.79
B 169452	61.41	16.65	7.76	.72	.58	.37	4.53	.80	.10	.01	.008	1252	44	83	317	34	14	12	6.7	.57	5.43	99.84
B 169455	59.73	13.90	10.95	1.07	.42	.27	3.64	1.07	.30	.02	.012	1249	63	76	163	22	14	16	8.3	.57	6.92	99.87
B 169460	65.71	15.51	5.25	1.54	.25	.43	3.80	.66	.11	.04	.008	946	57	92	173	27	<10	12	6.4	1.26	.94	99.86
B 169465	62.31	15.92	6.35	1.95	1.02	.55	3.66	.67	.14	.06	.005	805	56	134	273	26	<10	13	7.1	1.66	.66	99.89
B 169470	64.67	17.00	4.90	1.06	.49	.43	4.25	.82	.12	.01	.009	1028	42	105	174	36	13	16	5.9	.68	2.25	99.82
STANDARD SO-15/CSB	49.11	12.82	7.31	7.27	5.88	2.41	1.85	1.66	2.70	1.39	1.053	1972	82	396	912	22	26	12	5.9	2.45	5.39	99.76

GROUP 4A - 0.200 GM SAMPLE BY LIBO2 FUSION, ANALYSIS BY ICP-ES. LOI BY LOSS ON IGNITION.
TOTAL C & S BY LECO. (NOT INCLUDED IN THE SUM)
- SAMPLE TYPE: CORE PULP
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 6 2000 **DATE REPORT MAILED:** Oct 18/00 **SIGNED BY.** D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A001077R3

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 169447	.5	36	9	26	<.1	38	15	126	4.27	73	3	<2	6	13	.4	2.0	1.7	3	.25	.044	7	8	.13	81	.002	6	.30	.010	.18	2	4	.9	1	5.57	1
B 169450	1.9	33	25	35	.4	59	22	187	6.08	99	2	<2	5	45	.6	2.7	7.7	4	.52	.046	6	7	.18	72	.002	5	.23	.008	.14	1	1	2.0	2	7.27	<1
B 169453	.3	33	12	57	<.1	52	18	142	4.04	58	1	<2	4	14	.3	1.1	<.5	4	.21	.042	7	9	.20	65	.002	5	.27	.010	.17	2	1	.9	<1	5.36	1
B 169456	.3	30	11	81	.3	52	19	117	3.43	48	2	<2	4	17	.3	.7	<.5	4	.20	.047	6	10	.23	74	.002	2	.27	.011	.16	2	<1	1.3	1	3.91	<1
B 169459	1.5	20	17	72	.1	41	11	72	3.82	57	2	<2	4	12	.5	3.5	<.5	5	.16	.032	6	9	.11	64	.002	2	.23	.011	.13	3	5	.6	<1	5.42	1
B 169462	.8	37	6	72	<.1	35	14	433	3.73	7	2	<2	5	20	<.2	<.5	<.5	5	.47	.034	10	9	.91	46	.003	2	.32	.025	.17	1	<1	2.1	<1	.49	1
B 169465	.5	45	7	77	<.1	38	23	452	3.89	18	2	<2	5	29	<.2	<.5	<.5	5	.71	.039	8	7	.94	41	.002	<1	.29	.022	.16	1	<1	2.2	<1	.59	<1
RE B 169465	.5	47	8	82	<.1	39	18	454	3.82	10	2	<2	4	29	<.2	<.5	.5	6	.72	.040	8	7	.95	41	.002	3	.29	.023	.16	1	<1	2.2	<1	.60	1
B 169468	1.1	23	20	71	.2	31	13	43	2.86	24	1	<2	4	12	.2	1.7	<.5	3	.20	.034	6	7	.13	33	.002	2	.20	.011	.12	1	2	.8	<1	3.38	1
B 169471	1.4	35	24	63	.1	37	17	138	3.15	58	1	<2	3	30	.4	<.5	<.5	5	.31	.031	7	10	.47	61	.002	3	.25	.013	.14	2	<1	2.1	<1	2.15	1
STANDARD C3	27.8	67	36	171	5.3	38	13	834	3.29	59	24	2	20	28	25.7	17.5	23.1	81	.61	.095	19	183	.63	162	.092	23	1.85	.046	.17	16	1	4.3	<1	.03	8
STANDARD G-2	1.4	2	3	41	<.1	7	4	542	1.96	<1	2	<2	3	87	<.2	<.5	<.5	40	.71	.097	7	77	.60	246	.130	1	1.10	.160	.56	2	<1	2.5	<1	<.01	5

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns

DATE RECEIVED: OCT 6 2000 DATE REPORT MAILED: Oct 19/00 SIGNED BY: .....D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A001077R Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au* ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	Al %	Na %	K %	W ppm	Zr ppm	Ce ppm	Sn ppm	Y ppm	Nb ppm	Ta ppm	Be ppm	Sc ppm	Li ppm	S %	Rb ppm	Hf ppm
B 169401	1.2	45	9	26	<.2	43	20	1999	3.57	26	<1	<4	8	115	<.2	4	2	109	3.37	.061	36	75	1.19	734	.107	8.23	.239	3.33	6	53.7	64	10.1	6.7	4.6	<.5	3	18	7	.97	163	2
B 169402	1.0	66	9	54	<.2	166	33	1964	6.31	40	<1	<4	<1	252	.3	5	1	220	10.44	.095	15	293	3.85	822	.085	5.33	.152	2.44	3	9.5	30	3.2	6.1	1.0	<.5	2	24	8	.56	132	<1
B 169403	1.0	75	11	49	.2	106	31	2417	6.57	55	<1	<4	<1	209	.4	3	2	196	9.63	.080	13	150	3.76	619	.108	4.91	.094	2.32	5	16.4	26	3.5	6.5	1.4	<.5	1	21	8	.77	131	<1
B 169404	3.2	88	13	74	.2	86	31	2285	6.64	32	1	<4	<1	193	.3	4	2	165	9.07	.090	12	76	3.22	188	.132	5.03	.118	2.25	4	19.4	24	2.2	7.5	2.1	<.5	1	17	9	1.23	120	1
B 169405	1.8	43	10	51	<.2	46	23	946	4.60	21	<1	<4	2	140	<.2	4	2	125	5.48	.063	21	60	1.98	150	.164	5.23	.147	2.20	4	37.1	41	2.5	6.0	3.1	<.5	1	15	8	1.34	94	1
B 169406	6.4	77	14	86	.2	96	32	1126	7.05	9	2	<4	1	195	.3	5	1	177	8.94	.122	21	83	2.82	73	.188	5.73	.163	1.74	3	42.4	41	1.4	7.2	3.6	<.5	1	19	19	2.20	69	1
B 169407	2.1	99	35	72	.2	232	42	1199	5.92	16	1	<4	<1	276	.3	<1	<1	152	12.24	.074	15	309	4.10	1286	.057	5.59	.420	1.80	2	25.2	24	1.0	5.7	.8	<.5	1	24	12	.59	71	1
B 169408	2.3	56	23	64	.6	157	28	1272	6.36	48	<1	<4	<1	256	.3	<1	1	128	11.53	.060	9	227	3.65	162	.050	4.71	.169	1.68	<2	19.6	18	1.7	5.5	.9	<.5	1	21	11	1.02	67	<1
B 169409	3.9	78	9	65	.2	118	35	979	7.11	16	2	<4	<1	259	.4	2	<1	172	10.63	.072	11	180	3.31	88	.085	6.08	.707	1.98	<2	35.5	23	<.5	5.1	1.3	<.5	1	24	12	1.66	77	1
B 169410	4.8	84	10	63	<.2	72	32	1186	8.31	8	1	<4	1	269	.2	6	1	191	8.16	.189	14	82	2.39	57	.237	6.99	1.892	1.90	<2	35.4	31	<.5	6.6	5.0	.6	1	22	12	2.85	77	1
RE B 169410	5.0	83	11	66	<.2	77	33	1181	8.40	7	1	<4	1	265	.2	6	2	192	8.27	.194	20	80	2.41	58	.233	7.06	1.884	1.92	<2	36.8	42	.7	6.9	5.0	.7	1	22	12	2.90	78	1
RRE B 169410	5.1	83	11	60	<.2	75	33	1201	8.41	9	<1	<4	1	263	.4	5	<1	191	8.32	.195	19	78	2.42	54	.251	6.92	1.847	1.88	<2	37.9	42	.9	7.0	5.1	<.5	1	22	12	2.87	76	1
B 169411	5.5	144	15	98	<.2	59	39	1335	9.70	2	2	<4	1	241	.3	7	<1	222	6.48	.181	22	41	2.15	64	.244	7.78	.897	1.80	2	38.6	45	<.5	7.0	5.0	<.5	1	25	42	3.19	73	1
B 169412	1.9	135	13	124	<.2	80	51	1002	11.02	4	<1	<4	2	122	<.2	2	1	233	2.33	.189	26	41	1.78	44	.275	8.31	.134	1.37	4	8.5	50	<.5	5.4	5.8	.9	2	27	136	3.85	55	<1
B 169413	1.3	94	10	71	<.2	139	38	1106	7.02	10	<1	<4	3	291	.2	5	<1	166	5.71	.089	16	233	2.57	101	.104	6.98	.225	2.73	6	16.0	31	.7	4.9	1.7	<.5	2	26	37	1.89	131	1
B 169414	3.5	46	9	57	<.2	42	14	791	4.04	7	<1	<4	8	162	<.2	2	<1	67	2.67	.032	28	74	1.39	435	.078	5.78	.197	2.24	2	51.7	53	2.1	6.4	1.7	<.5	1	11	15	.86	91	1
B 169415	2.0	62	11	77	<.2	85	26	324	4.67	2	2	<4	11	106	<.2	1	<1	119	.61	.071	35	126	.92	248	.103	8.55	.292	3.22	2	82.3	64	2.0	5.8	2.2	.9	2	18	19	1.32	151	3
B 169416	2.0	28	13	209	<.2	46	14	405	3.79	3	2	<4	14	110	<.2	<1	<1	80	.87	.060	39	87	1.07	1810	.089	8.21	.294	3.08	<2	73.9	72	1.7	5.3	2.0	.6	2	14	13	.56	120	3
B 169417	1.5	78	14	101	.3	149	45	407	9.02	30	<1	<4	2	167	.5	4	2	269	2.60	.176	20	143	1.30	38	.204	9.56	.212	3.50	11	28.6	46	.6	7.6	3.6	1.0	3	28	18	4.63	161	1
B 169418	3.9	88	16	187	.2	59	38	156	10.34	8	<1	<4	<1	87	1.1	5	<1	198	.83	.247	11	45	.52	30	.181	7.97	.196	3.35	5	10.8	29	.5	5.8	3.4	1.0	2	22	11	8.57	141	<1
B 169419	2.2	59	80	78	2.1	125	75	686	14.78	28	<1	12	2	225	.5	2	6	375	2.95	.331	18	35	1.12	25	.318	11.09	.231	4.81	13	18.1	52	3.0	15.5	6.1	2.1	4	46	12	12.25	286	1
B 169420	2.1	42	56	120	2.5	110	58	330	11.83	15	<1	13	1	165	.5	1	5	467	1.77	.283	11	46	.79	33	.358	12.55	.243	5.67	12	31.1	34	2.5	11.1	5.8	2.6	4	43	17	9.97	326	1
B 169421	9.5	49	43	127	1.2	80	66	72	15.97	11	<1	<4	1	118	.7	3	5	429	.92	.309	8	49	.40	23	.299	11.96	.225	5.27	12	12.9	29	2.9	10.2	4.9	2.4	4	37	15	14.84	308	<1
B 169422	4.9	29	36	70	1.4	93	64	257	12.18	13	<1	10	1	176	2	1	5	315	1.86	.432	8	54	.67	36	.315	12.59	.255	5.67	9	21.6	25	2.3	13.4	5.7	1.7	4	33	18	10.48	315	<1
RE B 169422	4.7	34	37	74	1.4	96	67	260	12.38	11	<1	9	1	177	.3	1	6	316	1.88	.448	9	53	.67	43	.353	12.61	.255	5.68	10	22.7	28	3.4	13.9	6.7	1.9	5	33	18	10.84	321	1
RRE B 169422	4.8	29	37	59	1.5	95	65	252	12.66	12	<1	10	<1	179	<.2	1	5	317	1.84	.422	6	55	.67	32	.323	12.69	.255	5.69	10	19.6	20	2.4	12.4	5.9	2.4	4	34	18	10.89	299	1
B 169423	2.3	46	30	68	.9	134	84	187	13.12	16	<1	6	1	119	<.2	<1	5	407	1.19	.284	8	39	.51	28	.403	12.58	.267	5.61	14	23.1	26	4.0	9.8	7.0	1.6	4	38	16	11.44	305	<1
B 169424	4.5	28	21	53	.7	135	87	403	11.59	19	<1	5	1	182	<.2	<1	5	420	2.25	.367	10	49	.81	36	.355	12.46	.273	5.53	14	52.1	29	2.9	15.0	6.5	2.0	4	36	14	9.71	328	1
B 169425	1.9	4	3	41	<.2	61	51	586	5.59	16	<1	<4	1	191	<.2	<1	1	566	2.10	.339	12	40	.91	140	.590	14.43	.345	6.73	15	41.6	27	5.2	12.1	13.1	2.0	5	47	15	2.89	394	1
B 169426	1.8	4	9	21	.2	86	64	620	5.95	54	<1	<4	3	220	<.2	<1	2	478	2.71	.340	13	53	.98	107	.458	13.22	.329	6.11	13	16.8	28	3.6	12.7	12.2	2.1	5	45	13	3.49	377	1
B 169427	1.4	16	39	36	1.9	167	80	1745	12.62	60	<1	15	<1	345	.2	4	3	295	5.25	.110	10	110	2.15	50	.202	10.37	.264	4.44	10	15.2	23	4.3	12.4	3.6	1.3	4	38	10	9.29	313	1
B 169428	10.2	32	70	61	4.4	132	74	686	16.22	34	<1	40	<1	161	.4	4	7	335	2.25	.124	7	51	1.03	28	.223	11.44	.283	4.97	11	18.1	19	5.9	7.9	4.0	2.1	4	35	11	13.87	365	1
B 169429	5.9	41	109	57	4.7	186	99	746	17.44	88	<1	41	3	175	.3	5	7	332	2.39	.168	14	56	1.04	32	.326	10.39	.264	4.48	15	26.5	37	6.8	10.1	6.7	2.2	4	33	10	15.07	338	1
B 169430	4.2	9	17	30	1.9	96	56	843	8.72	26	<1	17	2	247	<.2	2	3	421	2.95	.205	15	90	1.24	81	.431	13.17	.366	5.91	14	21.3	31	4.4	10.5	9.1	1.8	5	44	14	4.97	422	<1
STANDARD CT3	26.2	63	39	179	5.5	36	11	947	4.15	59	22	<4	22	230	23.3	19	21	132	1.61	.091	26	252	.95	1041	.369	7.46	1.813	1.92	25	39.0	47	18.3	12.0	16.2	<.5	5	11	34	03	72	1
STANDARD G-2	2.3	<1	23	66	<.2	7	3	801	2.66	<2	2	<4	7	786	<.2	<1	1	60	3.17	.088	29	81	.77	1017	.256	9.36	2.705	3.03	2	6.7	55	.8	13.6	18.5	1.4	3	7	36	<.01	131	1

GROUP 1EX - 0.25 GM SAMPLE DIGESTED WITH HCLO4-HNO3-HCL-HF TO 10 ML. UPPER LIMITS - AG, AU, W = 200 PPM; MO, CO, CD, SB, BI, TH & U = 4,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM. DIGESTION IS PARTIAL FOR SOME MINERALS & MAY VOLATIZE SOME ELEMENTS, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE REJ. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAY 11 2000 DATE REPORT MAILED: May 26/2000 SIGNED BY ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

PA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au* ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	Al %	Na %	K %	W ppm	Zr ppm	Ce ppm	Sn ppm	Y ppm	Nb ppm	Ta ppm	Be ppm	Sc ppm	Li ppm	S %	Rb ppm	Hf ppm
B 169431	1.7	19	24	24	.4	149	71	447	10.39	37	<1	4	1	160	.3	3	6	352	1.81	.175	3	172	.79	135	.211	12.94	.393	5.93	10	7.7	11	2.6	6.6	2.7	1.2	4	42	16	7.31	415	<1
B 169432	1.7	20	35	24	1.2	127	68	1228	11.41	52	<1	9	1	280	.2	4	4	308	3.89	.149	9	159	1.48	63	.239	10.85	.338	4.80	11	14.2	23	3.2	11.4	3.5	.8	4	40	12	7.43	352	<1
B 169433	3.4	15	26	25	.8	79	66	1792	11.96	31	<1	6	<1	423	.3	2	4	353	6.07	.280	15	50	2.10	57	.330	9.76	.283	4.23	13	17.6	34	3.0	18.2	6.6	.5	4	40	9	7.12	326	<1
B 169434	1.8	31	59	25	2.2	85	78	1284	13.48	52	<1	15	1	311	.4	3	5	398	4.64	.251	11	41	1.57	41	.368	10.34	.290	4.46	16	19.8	29	4.7	14.6	6.6	.6	4	39	10	8.82	348	<1
B 169435	2.4	80	150	24	6.6	116	84	1579	20.39	91	<1	41	2	310	.4	4	11	241	5.14	.139	14	24	1.78	29	.197	6.21	.200	2.66	9	23.2	36	1.7	11.3	3.8	1.7	2	29	6	12.67	186	1
B 169436	1.7	72	133	31	4.3	166	89	916	20.95	61	1	23	2	204	.2	2	12	201	3.12	.124	9	41	1.10	54	.120	6.71	.230	2.80	7	23.5	23	1.5	7.0	2.0	<.5	3	24	8	13.47	192	1
B 169437	7.2	26	20	24	.6	66	54	1173	8.80	21	2	7	9	305	.3	2	3	225	3.91	.145	30	58	1.51	109	.244	12.17	.422	5.26	13	92.1	60	4.2	11.5	4.5	.7	5	28	14	5.43	360	3
B 169438	3.3	58	81	25	1.9	101	81	1174	14.52	35	<1	12	4	274	.4	5	7	284	3.87	.152	11	34	1.40	32	.262	9.73	.332	4.09	11	44.6	29	2.6	10.5	4.5	1.2	3	31	10	9.89	304	1
B 169439	1.6	3	4	24	<.2	27	27	1663	5.66	55	<1	<4	2	479	.2	1	1	349	5.66	.162	16	37	2.08	3017	.642	12.07	.401	5.21	16	32.8	29	2.0	13.3	14.6	<.5	4	38	13	1.97	370	2
B 169440	2.1	24	19	21	.3	66	41	1052	7.91	64	4	5	12	264	.4	2	2	158	3.05	.116	29	64	1.29	199	.144	13.86	.451	6.04	6	132.9	56	6.9	11.7	1.9	.6	5	25	17	4.98	408	5
B 169441	2.9	22	22	20	.2	99	60	412	11.26	49	3	<4	8	129	.2	3	4	175	1.15	.125	15	103	.65	91	.117	13.21	.417	5.89	6	145.0	33	7.6	9.3	1.0	2.1	5	23	17	8.52	400	5
B 169442	3.0	47	33	18	.8	73	37	602	10.31	24	3	12	8	157	.3	1	2	165	1.68	.102	14	78	.85	79	.107	13.07	.409	5.83	4	139.1	32	7.9	9.1	.7	.8	5	24	17	7.62	391	4
RE B 169442	2.9	44	34	16	.7	79	39	551	11.14	29	3	10	8	153	.6	1	3	174	1.55	.104	15	81	.81	85	.114	13.51	.421	6.00	5	145.4	34	7.2	9.2	.8	1.1	5	24	17	8.27	415	4
RRE B 169442	3.5	43	35	16	.6	81	41	547	11.07	26	3	9	8	156	.4	<1	2	181	1.56	.108	16	75	.83	87	.120	13.90	.434	6.19	5	150.6	35	8.7	9.6	.6	1.0	5	25	18	8.14	430	5
B 169443	1.9	27	14	21	.3	52	26	532	6.28	21	4	5	14	172	<.2	2	1	205	1.45	.125	34	94	.80	218	.193	15.39	.440	6.98	7	128.4	63	8.4	10.7	2.8	1.7	6	28	19	4.32	469	4
B 169444	1.3	12	12	16	<.2	29	18	214	4.11	30	5	<4	18	134	<.2	2	<1	169	.64	.111	46	111	.58	1234	.165	16.52	.438	7.92	6	165.0	77	8.6	9.6	2.4	1.4	7	27	20	2.75	500	5
B 169445	4.1	34	9	18	<.2	51	37	759	7.08	14	4	<4	12	168	.4	1	<1	224	2.26	.204	24	97	.96	127	.232	13.10	.305	5.91	10	116.7	46	7.3	12.6	4.3	.9	5	28	16	4.96	376	4
B 169446	4.5	65	13	23	<.2	66	34	305	6.02	11	5	<4	5	73	.5	3	2	205	.92	.116	10	83	.47	52	.126	5.83	.134	2.53	6	75.0	19	1.8	4.9	2.3	<.5	2	17	9	5.21	123	2
STANDARD CT3	26.3	64	40	180	5.7	37	12	990	4.41	63	23	<4	26	240	24.8	22	23	137	1.62	.098	27	258	.92	1077	.382	7.82	1.876	2.03	29	45.8	46	20.1	13.0	17.5	<.5	5	12	36	.03	76	1
STANDARD G-2	2.4	1	19	43	<.2	6	4	756	2.69	<2	1	<4	6	814	<.2	<1	<1	54	2.97	.094	28	72	.70	1049	.243	9.23	2.696	3.09	3	7.2	49	1.0	14.3	18.9	.8	3	7	36	<.01	146	<1

Sample type: CORE REJ Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All resul are considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A000960R

305 - 455 Granville St., Vancouver BC V6C 1T1

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 169701	4.9	8	24	39	1.1	172	62	2608	10.20	644	1	<2	3	262	.3	1.5	6.7	27	7.03	.124	3	28	2.63	81	.018	9	.61	.039	.33	2	<1	12.6	1	6.49	1
B 169702	3.9	5	15	40	.7	99	45	2440	6.07	301	2	2	5	205	<.2	.5	3.4	16	7.04	.077	3	19	2.48	163	.016	9	.65	.023	.36	1	<1	8.9	1	3.33	2
B 169703	5.2	18	16	47	.7	182	65	1954	8.28	436	1	<2	<1	267	.3	1.2	4.5	20	7.97	.071	2	31	2.92	167	.023	6	.64	.018	.35	1	<1	12.2	<1	4.66	2
B 169704	4.2	18	7	52	.4	130	48	1589	7.30	242	1	<2	<1	368	.9	.6	3.3	19	9.53	.077	2	23	3.60	209	.016	3	.53	.016	.30	1	<1	11.9	<1	2.63	1
B 169705	4.4	19	83	47	4.5	170	62	1480	11.85	526	1	13	1	318	.2	1.6	12.2	24	7.66	.100	2	30	2.80	169	.032	2	.65	.019	.35	2	<1	12.5	<1	7.75	1
B 169706	4.5	15	264	37	11.7	185	56	685	16.96	947	1	31	1	137	.3	<.5	26.6	15	2.48	.106	2	25	1.11	95	.022	4	.52	.012	.28	1	<1	6.2	<1	14.82	1
B 169707	4.8	32	453	34	21.8	284	96	75	29.33	1592	<1	47	1	27	.3	1.1	47.7	14	.36	.064	2	13	.09	38	.016	8	.38	.011	.21	3	<1	2.2	3	35.00	<1
B 169708	4.3	30	120	30	10.2	235	71	570	13.64	943	<1	33	1	102	.3	1.2	13.4	15	1.88	.073	2	39	.71	77	.019	4	.54	.017	.30	1	<1	5.3	<1	15.00	1
B 169709	2.5	38	390	46	22.1	338	118	240	31.89	1845	<1	51	2	54	.9	<.5	52.0	16	.79	.079	1	13	.25	40	.021	8	.40	.011	.22	4	<1	3.3	1	37.00	1
B 169710	6.5	34	158	46	9.7	161	71	503	22.73	1109	1	16	1	96	.3	1.5	31.1	12	1.36	.145	2	15	.61	66	.012	9	.42	.012	.24	1	<1	4.1	<1	26.00	2
B 169711	3.2	34	98	46	6.5	194	83	997	17.79	937	1	7	1	198	.4	.7	23.0	17	3.31	.140	2	18	1.45	88	.019	7	.58	.016	.32	3	<1	7.4	<1	16.34	2
B 169712	3.8	17	5	36	.4	138	54	1623	8.24	669	1	<2	2	311	.2	2.7	1.9	22	6.19	.158	2	24	2.16	160	.018	3	.66	.029	.36	1	<1	10.5	<1	5.37	2
B 169713	4.2	28	57	28	7.3	84	38	1040	12.65	780	<1	33	3	181	.3	1.0	14.4	13	3.15	.108	3	11	1.26	115	.014	3	.65	.023	.36	3	<1	6.2	<1	10.70	1
B 169714	7.4	20	16	30	1.7	250	59	606	12.41	1073	<1	12	1	107	.5	.5	5.4	18	1.77	.120	2	41	.68	93	.021	1	.64	.029	.34	1	<1	5.1	<1	11.74	1
RE B 169714	7.3	20	15	29	1.5	244	57	604	12.55	1068	<1	9	2	107	.4	.6	5.0	18	1.78	.116	2	41	.68	94	.028	1	.69	.032	.36	1	<1	5.2	<1	11.75	1
B 169715	1.1	9	3	13	.2	21	16	915	2.07	112	2	<2	7	173	.5	<.5	<.5	11	2.34	.080	8	8	.90	155	.010	8	.81	.030	.43	1	<1	5.8	<1	.92	2
B 169716	6.5	55	104	58	9.6	170	72	1145	17.00	1009	1	27	2	215	.3	.7	21.7	19	4.03	.122	2	19	1.66	111	.027	6	.58	.019	.32	1	<1	7.6	<1	14.93	2
B 169717	1.5	13	7	20	.4	60	22	1365	4.06	234	1	<2	5	188	.2	<.5	1.4	12	3.31	.050	5	11	1.24	146	.011	6	.74	.026	.41	1	<1	5.7	<1	2.52	2
B 169718	1.3	20	4	15	.2	63	28	728	4.14	418	<1	<2	6	136	<.2	<.5	.7	9	1.88	.080	7	9	.65	127	.006	6	.66	.020	.38	1	<1	5.3	<1	3.46	2
B 169719	1.0	13	2	13	.1	28	17	1069	2.52	179	1	<2	4	187	.7	<.5	<.5	14	2.83	.122	7	11	1.01	140	.015	11	.78	.020	.42	1	<1	6.4	<1	1.28	2
STANDARD C3	27.0	72	34	171	5.3	36	12	790	3.24	58	23	<2	21	26	22.7	18.0	22.5	76	.55	.094	17	168	.59	156	.082	20	1.76	.040	.16	16	1	4.1	1	.04	9
STANDARD G-2	1.5	2	2	44	<.1	7	4	537	1.92	1	2	<2	3	78	<.2	<.5	<.5	39	.65	.100	7	74	.59	241	.124	2	1.06	.130	.54	2	<1	2.4	<1	.02	5

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 6 2000 DATE REPORT MAILED: Oct 14/00 SIGNED BY: C. Leong ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ____

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A000958R2 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 169629	5.8	49	17	87	.2	64	17	847	3.83	130	2	<2	6	126	.8	<.5	.7	7	4.85	.061	7	18	1.54	199	.003	4	.43	.016	.28	2	<1	4.0	<1	.99	1
B 169630	4.5	49	10	78	.6	88	39	2098	7.87	136	2	2	1	217	.7	1.3	3.6	19	9.26	.122	2	17	2.97	177	.005	5	.46	.015	.31	2	<1	9.0	<1	2.70	1
B 169631	3.4	31	12	45	.7	96	58	2154	9.29	334	1	3	2	138	.3	1.3	10.0	24	4.91	.183	2	10	1.45	111	.009	5	.61	.021	.43	1	<1	7.4	1	6.15	2
B 169632	4.2	5	8	67	.7	75	39	3914	7.32	114	2	<2	1	275	.5	.5	8.0	19	12.57	.078	1	18	3.75	142	.005	4	.42	.015	.31	<1	1	11.4	3	1.60	<1
B 169633	5.3	11	27	63	1.5	167	74	2655	13.83	614	2	8	1	183	.4	1.4	28.6	24	6.43	.227	3	11	2.00	86	.012	8	.64	.015	.43	1	<1	8.1	<1	9.74	2
B 169634	.7	2	13	53	.3	17	8	2486	2.78	57	4	<2	9	143	.3	.9	1.3	9	4.32	.073	11	7	1.46	97	.001	8	.49	.016	.35	1	<1	4.1	2	.70	1
B 169635	2.6	60	18	67	.4	160	47	965	5.73	344	1	<2	<1	242	.3	1.5	.8	19	5.30	.141	2	31	2.11	156	.004	8	.52	.019	.31	1	<1	8.9	<1	2.38	1
B 169636	3.6	123	17	192	.5	90	37	359	7.82	84	2	<2	2	113	.8	3.4	<.5	25	2.07	.301	3	13	.89	90	.009	7	.71	.023	.39	2	1	5.8	<1	6.11	2
B 169637	2.2	168	10	156	.3	39	32	241	3.78	31	1	<2	2	98	.5	1.8	<.5	32	1.71	.278	7	10	.55	183	.020	11	.81	.029	.43	1	2	5.1	<1	2.51	2
B 169638	1.2	188	10	292	.4	43	43	171	3.33	26	1	<2	1	85	.9	1.0	<.5	29	1.33	.267	7	12	.31	78	.005	8	.68	.063	.33	3	1	4.8	<1	2.74	2
B 169639	5.7	164	7	238	.2	54	47	285	3.67	27	1	<2	1	112	.7	1.4	<.5	29	1.67	.216	4	12	.48	90	.004	5	.56	.054	.29	1	1	6.1	<1	2.46	2
B 169640	2.8	46	8	101	.2	32	36	516	4.16	21	1	<2	1	99	.3	.7	<.5	21	1.63	.262	7	11	.65	145	.005	5	.69	.031	.36	2	<1	4.3	<1	1.35	2
B 169641	1.9	98	6	102	.2	38	41	1180	8.00	14	<1	<2	1	59	<.2	.6	<.5	28	.97	.324	11	8	1.17	229	.007	6	.74	.050	.40	1	<1	5.4	1	.99	3
B 169642	3.2	127	6	102	.2	61	49	822	6.98	32	<1	<2	1	72	.2	.9	<.5	24	1.39	.300	6	11	1.09	120	.006	9	.69	.043	.38	<1	1	5.1	<1	2.41	2
B 169643	2.4	113	5	143	.1	45	42	879	7.57	14	<1	<2	1	60	.2	1.0	<.5	33	1.20	.229	6	10	.93	118	.006	4	.64	.050	.34	2	1	6.8	<1	1.84	2
B 169644	2.5	132	6	127	.1	58	49	1368	9.15	10	<1	<2	1	40	<.2	.8	<.5	31	.79	.232	7	10	1.02	111	.006	6	.61	.059	.32	<1	1	6.5	1	2.20	2
B 169645	2.4	129	4	124	.1	56	47	1224	7.85	10	<1	<2	1	65	<.2	<.5	<.5	37	1.40	.233	6	9	1.22	177	.010	5	.67	.061	.34	<1	1	7.2	<1	1.47	2
RE B 169645	2.3	124	4	119	.1	53	47	1205	7.70	11	<1	<2	1	64	<.2	<.5	<.5	35	1.39	.234	6	9	1.21	170	.012	3	.66	.061	.34	<1	1	7.2	<1	1.46	2
B 169646	.4	123	3	109	.1	97	43	1599	7.84	2	<1	<2	1	52	<.2	<.5	<.5	31	1.35	.133	4	24	1.44	211	.002	3	.57	.072	.20	1	<1	8.6	<1	.67	2
B 169647	2.0	210	5	122	.1	86	49	1485	9.71	9	<1	<2	<1	46	<.2	.9	<.5	31	1.21	.145	3	13	1.28	69	.003	4	.49	.066	.18	<1	<1	8.4	2	3.91	1
B 169648	.9	164	5	141	.2	64	46	1101	8.91	16	<1	<2	2	84	.2	.9	<.5	30	2.51	.168	2	10	1.39	79	.003	3	.59	.055	.22	2	<1	8.0	1	3.98	2
B 169649	2.3	148	3	93	.1	61	49	1525	10.33	18	<1	<2	1	58	<.2	.5	<.5	48	1.55	.204	6	12	1.32	99	.005	<1	.68	.085	.18	<1	1	8.0	2	3.61	2
B 169650	1.1	149	5	85	.1	59	49	1250	9.88	20	<1	<2	1	50	<.2	1.6	<.5	44	1.15	.234	6	11	1.06	90	.003	3	.70	.110	.19	1	<1	7.9	2	4.24	3
B 169651	2.4	153	4	79	.1	62	43	1488	9.53	11	<1	<2	1	60	<.2	.7	<.5	41	1.41	.214	5	10	1.31	108	.002	1	.61	.107	.17	1	<1	8.0	1	2.77	1
B 169652	1.2	176	6	96	.2	112	67	1565	12.22	46	1	<2	1	149	.3	3.3	<.5	33	5.41	.073	1	25	2.44	83	.001	<1	.48	.065	.15	1	<1	8.4	3	6.35	1
B 169653	1.6	174	2	82	.1	81	48	1539	8.45	4	1	<2	2	67	<.2	<.5	.5	38	1.77	.160	5	11	1.79	221	.004	<1	.60	.096	.17	<1	<1	9.1	<1	.92	2
B 169654	.8	162	4	94	.1	85	54	1606	10.44	12	<1	<2	<1	102	<.2	<.5	<.5	55	2.87	.130	2	16	2.21	200	.008	<1	.95	.095	.18	1	<1	10.0	2	2.22	3
B 169655	1.9	140	2	88	.1	83	48	1214	8.04	5	<1	<2	<1	97	.2	<.5	<.5	51	2.74	.130	3	20	1.98	203	.005	4	.94	.059	.15	<1	<1	9.5	2	.97	4
B 169656	1.8	183	7	103	.2	74	57	1694	13.00	49	1	<2	1	193	.5	3.7	<.5	38	6.34	.086	1	15	2.58	106	.003	3	.64	.036	.14	1	2	7.8	3	7.18	2
B 169657	4.1	277	4	142	.2	113	78	1347	8.24	18	<1	<2	<1	112	.3	1.1	<.5	52	3.18	.152	3	16	1.91	217	.006	1	1.05	.057	.18	<1	3	8.1	1	1.62	3
B 169658	2.2	125	2	147	.2	88	65	1109	7.12	13	<1	<2	<1	182	.3	<.5	<.5	34	4.66	.123	4	15	2.44	262	.004	2	1.15	.032	.18	<1	1	7.7	<1	.41	3
B 169659	.7	204	2	96	.1	64	45	1302	7.66	4	<1	<2	2	77	<.2	<.5	<.5	34	1.73	.157	7	13	1.70	338	.007	3	.99	.061	.25	1	<1	7.8	<1	.44	4
B 169720	4.4	15	11	22	.1	61	15	370	3.51	178	2	<2	7	66	.8	.7	3.8	12	.98	.100	9	16	.32	127	.001	9	.43	.012	.27	2	<1	2.7	<1	3.16	1
B 169721	2.5	73	14	26	.3	82	29	791	5.29	301	2	<2	4	112	<.2	.8	2.2	10	1.86	.112	6	18	.66	83	.002	8	.51	.013	.33	4	<1	4.9	<1	5.05	2
B 169722	4.6	49	13	60	.1	123	43	355	5.61	154	1	<2	3	55	.8	2.2	3.2	13	.97	.078	4	24	.35	64	.003	7	.49	.013	.31	2	3	2.6	1	5.73	1
STANDARD C3	27.6	69	36	182	5.3	38	12	857	3.46	60	25	<2	23	31	23.8	17.0	23.8	87	.63	.098	20	179	.65	169	.096	23	1.85	.045	.18	15	1	4.8	<1	.03	8
STANDARD G-2	1.7	2	3	48	<.1	8	4	604	2.16	1	2	<2	5	81	<.2	<.5	<.5	45	.73	.107	8	82	.66	247	.137	<1	.98	.096	.54	2	<1	2.8	<1	<.01	5

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns

DATE RECEIVED: OCT 6 2000 DATE REPORT MAILED: Oct 16/00 SIGNED BY: D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 169723	.7	32	7	101	<.1	36	13	140	2.88	38	<1	<2	5	24	.4	<.5	.5	4	.32	.040	10	15	.17	136	.003	6	.48	.013	.27	5	2	1.2	1	2.63	1
B 169724	2.9	23	7	56	<.1	39	12	106	3.20	51	<1	<2	6	18	.3	.8	1.2	4	.20	.040	11	14	.15	142	.002	7	.48	.012	.27	2	2	1.2	4	2.92	1
RE B 169724	2.8	23	7	54	<.1	39	12	108	3.04	51	<1	<2	7	17	.3	.6	1.3	4	.20	.040	10	14	.15	139	.003	5	.47	.012	.27	1	2	1.1	5	2.88	1

Sample type: CORE PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A001008R2 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 169731	.6	121	24	134	.2	77	42	1537	6.65	157	1	<2	1	184	.8	1.2	<.5	20	5.83	.147	2	9	2.54	100	.007	9	.54	.027	.28	2	<1	6.8	<1	1.04	2
B 169732	2.5	46	14	78	.1	181	38	2500	6.57	282	1	<2	<1	288	.3	2.5	.6	14	11.39	.070	2	37	4.91	52	.004	7	.27	.017	.16	1	<1	8.4	<1	.47	1
B 169733	.9	84	11	58	<.1	66	27	1993	5.63	100	<1	<2	1	286	.4	<.5	.9	14	8.74	.119	2	9	3.60	77	.005	11	.38	.020	.22	2	<1	7.1	<1	.76	1
B 169734	3.8	106	16	87	.1	78	34	1210	5.91	81	1	<2	1	172	<.2	.8	<.5	14	6.24	.118	2	14	2.43	109	.004	6	.42	.024	.20	1	<1	6.2	<1	1.13	1
B 169735	2.7	80	12	85	.1	147	36	1112	6.07	59	1	<2	1	284	<.2	.6	<.5	14	11.69	.086	2	21	2.82	121	.003	10	.32	.025	.17	1	<1	8.6	<1	1.07	1
B 169736	4.9	59	11	71	<.1	115	34	975	5.58	129	1	<2	1	218	.2	1.1	.9	11	7.92	.069	2	20	2.67	137	.003	8	.32	.016	.17	1	<1	6.9	<1	1.34	1
B 169737	3.2	146	13	75	.2	68	42	1576	8.04	102	1	<2	1	186	.4	.6	1.3	19	5.85	.138	2	10	1.97	137	.008	5	.48	.015	.25	3	<1	6.1	<1	3.11	1
B 169738	4.5	24	10	54	<.1	149	38	1938	5.81	254	1	<2	1	258	.3	<.5	2.1	12	8.32	.064	1	24	3.12	113	.003	5	.35	.012	.20	1	<1	7.7	<1	1.14	1
B 169739	4.6	13	12	41	.1	54	15	2819	5.65	116	2	<2	3	202	.2	<.5	1.9	17	7.10	.183	3	9	2.40	126	.008	10	.55	.016	.31	2	<1	7.1	<1	1.71	2
B 169740	1.6	2	5	12	<.1	26	7	1401	2.66	105	3	<2	6	90	<.2	<.5	<.5	8	2.50	.070	11	6	.92	111	.001	5	.44	.008	.26	1	<1	4.8	<1	1.52	1
B 169741	.6	1	4	10	<.1	45	9	788	1.79	133	3	<2	6	46	<.2	<.5	<.5	8	1.58	.097	14	7	.60	149	.003	7	.61	.014	.35	1	<1	3.4	<1	1.15	1
B 169742	8.0	18	144	42	2.3	167	102	76	22.25	685	2	10	2	37	<.2	4.7	36.0	17	.81	.310	5	18	.04	34	.003	5	.44	.006	.23	3	20	2.6	<1	26.00	<1
B 169743	2.5	9	37	28	.5	173	80	1500	10.13	483	2	3	2	104	<.2	3.8	11.8	16	2.73	.214	5	25	1.10	66	.002	6	.54	.009	.29	2	13	6.9	1	8.50	1
B 169744	2.2	13	111	34	1.5	235	123	470	16.50	857	2	7	1	49	<.2	1.6	18.0	18	1.26	.322	5	14	.29	46	.005	4	.60	.010	.30	5	3	3.3	<1	18.00	1
B 169745	9.3	24	37	23	.4	92	42	994	6.15	383	2	3	2	87	<.2	<.5	2.3	22	2.30	.413	8	10	.48	82	.006	7	.72	.015	.37	2	<1	5.0	<1	5.50	2
RE B 169745	9.3	22	37	21	.4	92	42	975	6.10	380	2	<2	1	84	<.2	<.5	2.6	22	2.25	.407	7	11	.47	71	.005	10	.69	.015	.36	2	<1	4.9	<1	5.30	1
B 169746	2.1	7	31	23	.4	37	18	2277	4.08	165	1	4	1	117	<.2	<.5	1.2	27	3.85	.295	6	5	1.15	158	.006	13	.66	.018	.35	2	<1	8.0	<1	1.93	2
B 169747	4.5	28	120	17	1.8	139	71	1355	13.60	812	1	16	1	65	<.2	<.5	5.6	22	1.90	.279	6	14	.67	59	.008	4	.61	.011	.32	2	2	5.1	<1	12.31	1
B 169748	1.7	77	382	18	9.8	318	128	649	26.63	1488	<1	104	2	43	.2	2.2	28.7	16	1.01	.106	4	15	.38	36	.004	7	.37	.006	.20	6	3	4.9	<1	28.00	<1
B 169749	5.3	56	437	50	11.9	243	95	416	23.69	1101	1	106	1	46	.4	1.3	31.3	20	1.05	.210	5	17	.27	28	.004	5	.43	.007	.21	3	3	3.8	1	25.00	<1
B 169750	.6	39	104	51	2.5	178	73	2061	9.80	575	1	28	1	75	<.2	1.0	4.8	20	2.96	.140	5	19	1.10	67	.004	4	.57	.017	.31	3	1	7.3	1	8.42	1
B 169751	3.3	36	138	21	2.8	205	94	1342	14.07	933	1	26	1	90	<.2	<.5	9.8	21	2.76	.111	5	18	1.00	55	.005	7	.53	.011	.29	2	1	8.6	<1	12.64	1
B 169752	.7	26	97	32	2.1	137	72	2064	11.05	583	1	17	1	133	<.2	.5	7.7	19	3.72	.137	4	16	1.44	75	.004	4	.57	.014	.32	3	3	9.0	1	8.80	1
B 169753	3.4	47	146	19	4.8	151	71	1006	12.95	733	1	40	1	73	<.2	1.7	8.3	24	2.13	.178	5	15	.76	71	.015	7	.68	.012	.35	2	3	5.9	<1	11.98	1
B 169754	1.6	39	204	26	8.8	84	51	733	19.50	633	1	38	2	141	<.2	1.0	16.3	26	2.20	.292	6	10	.79	36	.008	7	.61	.011	.31	4	3	8.8	<1	19.00	1
B 169755	1.8	18	97	12	6.6	206	91	256	14.40	810	1	36	3	55	<.2	4.4	8.3	17	.86	.176	6	12	.19	41	.004	6	.56	.014	.28	3	5	3.8	<1	15.00	1
B 169756	5.6	23	78	22	1.8	137	47	100	14.79	463	2	4	6	30	<.2	5.0	9.7	7	.36	.071	8	15	.09	34	.001	4	.38	.006	.21	2	7	1.5	<1	16.00	<1
B 169757	2.6	19	27	28	.5	81	30	372	6.71	171	2	<2	8	75	.3	1.8	11.9	11	.98	.152	10	12	.26	50	.001	6	.55	.013	.30	4	1	3.5	<1	7.46	1
B 169758	9.5	99	11	184	.2	120	32	602	4.49	234	2	<2	2	130	.7	1.6	.6	18	2.18	.129	6	31	1.00	100	.002	4	.44	.010	.24	3	<1	4.3	<1	2.92	1
B 169759	.6	125	16	113	.2	163	44	1551	6.75	305	1	<2	1	271	.2	2.3	<.5	15	5.89	.044	1	21	2.72	93	.001	4	.39	.012	.23	3	<1	9.8	<1	2.90	1
B 169760	5.1	95	12	180	.1	147	53	494	5.51	166	2	<2	1	89	.6	2.8	<.5	15	2.11	.112	5	34	.90	81	.003	7	.50	.011	.26	2	2	4.5	1	4.89	1
B 169761	.8	39	12	85	<.1	54	21	272	3.73	67	2	<2	3	53	<.2	1.8	<.5	3	1.15	.081	11	13	.52	106	.002	6	.46	.011	.25	5	<1	2.0	<1	2.96	<1
B 169762	5.2	36	15	54	.2	36	12	104	2.74	134	2	<2	5	20	<.2	.5	<.5	3	.23	.038	13	21	.23	105	.001	3	.39	.010	.22	2	<1	1.2	1	1.84	<1
B 169763	.5	28	9	39	.1	34	13	545	3.16	77	2	<2	5	57	<.2	.7	<.5	4	1.25	.036	13	13	.89	96	.001	4	.40	.009	.24	5	<1	2.5	<1	.82	1
B 169764	4.7	26	9	39	.2	38	13	715	3.05	195	2	<2	4	102	.2	.5	<.5	4	1.89	.040	9	20	.88	99	.001	11	.35	.006	.21	2	<1	3.2	<1	1.58	1
STANDARD C3	27.2	67	36	172	5.5	36	12	796	3.42	60	24	3	21	29	22.4	17.3	23.3	80	.59	.095	21	177	.62	161	.081	23	1.82	.039	.17	16	1	4.5	<1	.03	6
STANDARD G-2	1.5	3	3	44	<.1	7	4	548	2.02	<1	3	<2	5	74	<.2	<.5	<.5	41	.67	.100	10	78	.62	237	.125	2	.96	.091	.50	2	<1	2.7	<1	<.01	4

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 6 2000 DATE REPORT MAILED: Oct 14/00 SIGNED BY: ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 169765	7.2	2	5	11	.1	29	19	785	3.71	206	4	<2	12	197	<.2	<.5	.5	19	2.41	.539	21	14	.51	95	.001	14	.77	.014	.38	2	<1	5.8	<1	3.26	1
B 169766	1.9	5	15	23	.4	41	21	207	4.72	263	4	2	9	42	<.2	.8	<.5	5	.59	.066	13	9	.18	57	<.001	7	.42	.008	.23	2	<1	2.4	<1	5.06	<1
B 169767	2.2	5	11	9	.5	54	30	668	6.86	381	4	5	8	52	<.2	<.5	1.0	6	1.27	.067	9	10	.45	58	<.001	7	.40	.007	.23	2	<1	3.9	<1	6.93	<1
B 169768	.2	6	30	<1	3.3	132	93	82	34.35	1956	2	12	3	15	<.2	<.5	12.7	<1	.25	.019	4	11	.08	19	.001	12	.18	.005	.09	5	<1	.2	<1	38.00	<1
B 169769	1.8	3	7	8	.1	29	19	366	3.31	148	4	<2	7	29	<.2	<.5	1.5	4	.68	.078	13	7	.21	83	<.001	8	.41	.007	.23	2	1	2.4	<1	3.58	<1
B 169770	1.1	7	13	10	.1	52	28	283	4.63	167	4	<2	5	28	<.2	1.0	2.6	4	.57	.075	12	8	.16	76	<.001	5	.43	.007	.24	2	2	2.1	1	5.23	<1
B 169771	1.7	12	27	16	.4	70	34	246	6.24	273	3	6	6	38	<.2	.9	2.0	6	.60	.096	11	10	.16	39	.001	6	.51	.009	.27	2	2	2.1	1	6.67	1
B 169772	.7	6	11	11	.1	54	30	773	4.92	167	5	<2	6	42	<.2	<.5	4.5	6	1.17	.079	9	6	.38	76	.001	8	.49	.011	.28	2	2	2.5	1	4.90	1
B 169773	2.1	8	19	18	.2	66	34	1016	7.17	233	4	<2	7	41	.2	1.8	4.7	5	1.30	.072	9	9	.47	59	.001	6	.48	.009	.27	2	2	3.8	3	7.00	1
B 169774	1.1	11	16	42	.1	55	23	1444	6.16	264	3	<2	7	143	.2	<.5	.8	9	2.95	.054	10	9	1.12	61	<.001	9	.52	.012	.29	69	<1	6.6	<1	4.94	1
B 169775	4.6	13	11	24	.1	62	21	817	4.36	233	2	<2	6	103	<.2	<.5	.8	5	1.96	.057	12	17	.74	84	<.001	8	.43	.009	.24	8	<1	4.3	<1	3.72	<1
B 169776	1.1	14	11	15	.1	31	15	1113	3.38	143	3	<2	7	109	<.2	<.5	.7	6	2.29	.059	12	12	.91	117	<.001	9	.43	.011	.25	6	<1	4.2	<1	2.23	1
B 169777	6.2	2	5	6	.2	62	50	236	12.06	586	5	<2	11	29	<.2	<.5	1.8	5	.63	.110	9	16	.15	52	.001	5	.48	.008	.26	3	<1	1.7	<1	11.38	<1
B 169778	2.5	3	7	12	.1	42	28	1424	7.13	368	4	<2	9	117	<.2	<.5	2.1	10	2.77	.118	12	10	.99	60	.001	10	.51	.010	.28	5	<1	5.9	<1	6.13	1
B 169779	2.2	5	8	16	.1	70	27	1214	7.52	263	4	<2	10	159	<.2	<.5	1.8	6	2.88	.060	8	11	1.16	78	<.001	7	.47	.010	.27	2	<1	6.0	1	5.44	1
B 169780	1.1	3	7	21	<.1	33	17	2083	5.84	225	5	<2	6	248	.3	1.1	<.5	10	5.34	.091	5	7	1.87	110	.001	12	.56	.012	.32	2	<1	8.9	<1	3.30	1
RE B 169780	1.4	3	7	22	<.1	34	18	2049	5.77	228	5	<2	6	244	.3	<.5	<.5	8	5.28	.094	5	7	1.84	114	.001	9	.55	.012	.32	2	<1	8.8	<1	3.24	2
B 169781	2.1	6	4	21	<.1	31	17	1768	5.32	211	3	<2	5	308	.2	.6	<.5	13	5.34	.213	4	8	1.78	122	.001	9	.55	.011	.30	2	<1	9.2	1	2.89	2
B 169782	2.4	24	11	20	.1	73	48	476	7.90	401	3	<2	2	165	<.2	.7	10.4	24	2.97	.629	6	12	.62	43	.002	8	.80	.013	.39	3	<1	7.5	1	6.94	2
B 169783	5.1	10	6	12	.1	109	63	806	9.97	615	4	<2	2	120	<.2	<.5	3.0	34	2.55	.431	6	19	.69	54	.002	7	.73	.013	.36	4	<1	7.6	<1	8.74	2
B 169784	4.0	25	9	18	.2	202	91	1009	6.66	664	3	<2	1	106	<.2	<.5	.9	19	2.73	.175	4	29	.94	70	.001	10	.53	.011	.28	2	<1	7.1	1	5.75	1
B 169785	1.3	33	11	34	.2	66	55	1746	7.66	294	2	<2	3	188	<.2	<.5	1.0	11	3.89	.115	6	13	1.58	54	.001	6	.50	.013	.28	188	<1	6.1	<1	5.34	1
STANDARD C3	27.4	70	35	174	5.3	37	12	800	3.36	58	26	3	21	30	22.8	16.3	23.2	80	.60	.096	21	180	.62	163	.086	23	1.84	.040	.17	15	1	4.6	<1	.03	7
STANDARD G-2	1.5	3	2	45	<.1	7	4	543	2.02	<1	3	<2	4	72	<.2	<.5	<.5	40	.66	.103	10	80	.61	236	.125	<1	.93	.079	.48	2	<1	2.6	<1	<.01	4

Sample type: CORE PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD 2K File # A001127R Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 169486	3.9	22	16	54	.7	130	48	1852	8.21	299	1	4	1	238	.3	1.2	3.3	14	8.51	.124	2	11	2.79	80	.008	3	.23	.010	.15	1	<1	7.5	<1	4.24	<1
B 169487	6.4	20	11	82	.5	104	40	2214	8.34	144	1	<2	2	358	.6	.5	2.8	14	10.18	.115	2	10	3.38	86	.008	5	.23	.011	.16	1	<1	9.7	<1	3.07	<1
B 169488	6.2	50	21	80	.5	73	54	1795	11.08	174	<1	<2	<1	218	.7	3.1	3.3	18	6.14	.185	1	5	2.06	50	.008	4	.27	.011	.18	1	<1	7.7	<1	7.15	1
B 169489	.7	40	9	62	.2	55	30	905	4.64	258	1	<2	3	161	.3	< 5	.5	4	2.12	.041	3	5	1.22	73	.001	4	.20	.011	.14	1	<1	3.1	<1	2.32	<1
B 169490	.3	41	9	58	.1	40	19	839	4.42	192	1	<2	4	134	.9	<.5	<.5	5	1.80	.036	4	6	1.18	54	.001	5	.21	.011	.14	1	<1	3.2	<1	1.68	<1
B 169491	.4	51	25	86	<.1	57	26	430	5.17	164	1	<2	3	20	.8	<.5	<.5	5	.31	.107	7	5	.96	58	.001	9	.25	.014	.17	1	<1	1.6	<1	1.72	<1
B 169492	.5	47	11	130	<.1	59	20	809	5.21	85	1	<2	3	39	.5	<.5	<.5	5	.80	.086	7	11	1.54	60	.003	3	.27	.014	.16	1	<1	2.9	<1	.51	1
B 169493	.7	13	5	40	<.1	48	20	937	5.15	107	1	<2	6	73	.4	<.5	<.5	5	1.10	.052	8	7	1.47	61	.001	11	.25	.013	.17	1	<1	3.6	<1	.96	<1
B 169494	1.0	20	12	48	<.1	40	15	556	4.36	103	1	<2	3	108	.5	<.5	.8	5	1.86	.047	4	6	1.11	62	.001	7	.21	.010	.14	1	<1	2.3	<1	2.52	<1
B 169495	.5	35	18	79	.2	36	14	193	3.09	60	1	<2	3	23	.4	<.5	<.5	3	.36	.043	6	8	.58	74	.001	3	.21	.010	.14	2	<1	1.3	<1	1.49	<1
B 169496	.6	16	10	58	<.1	22	7	164	2.49	46	1	<2	5	10	.3	< 5	<.5	3	.19	.034	9	7	.53	85	.001	3	.24	.014	.15	1	<1	1.1	<1	1.00	<1
B 169497	1.8	22	9	59	<.1	48	18	794	4.90	85	2	<2	4	89	.5	<.5	<.5	5	1.25	.071	6	7	1.39	119	.002	5	.33	.014	.21	2	<1	3.2	<1	1.24	1
B 169498	.6	20	6	43	.1	47	19	832	4.66	100	2	<2	4	61	.5	<.5	<.5	5	.85	.069	6	6	1.22	91	.002	3	.28	.011	.18	1	<1	2.6	<1	1.09	<1
B 169499	.3	8	2	33	<.1	39	15	1033	4.74	80	4	<2	7	111	.3	<.5	<.5	5	1.16	.123	8	3	1.40	78	.002	7	.28	.012	.17	<1	<1	3.9	<1	.98	<1
B 169500	1.1	30	7	57	<.1	43	19	619	4.33	63	1	<2	2	71	.3	<.5	<.5	5	1.62	.042	5	5	1.08	71	.001	2	.22	.012	.15	1	<1	1.8	<1	1.73	<1
B 169786	2.0	58	6	82	<.1	56	20	519	4.42	21	1	<2	4	29	<.2	<.5	<.5	4	.71	.044	7	7	1.07	60	.001	6	.21	.013	.14	1	<1	1.7	<1	.99	<1
B 169787	1.0	31	3	81	<.1	37	15	394	3.96	21	2	<2	5	8	<.2	<.5	<.5	3	.15	.036	10	5	.99	57	.001	3	.19	.012	.14	2	<1	1.4	<1	.64	1
B 169788	.9	40	4	77	.2	66	24	795	5.63	24	1	<2	15	179	.2	1.3	.7	9	6.08	.088	4	12	2.72	87	.002	9	.21	.013	.13	1	<1	4.0	<1	1.06	<1
B 169789	1.2	98	2	103	.1	189	56	643	5.66	52	1	<2	10	65	.2	<.5	<.5	13	1.63	.116	2	17	1.73	127	.003	3	.28	.012	.17	1	<1	4.8	<1	1.12	1
B 169790	1.6	91	11	188	.1	69	35	178	6.24	70	<1	<2	<1	89	.8	2.7	<.5	13	1.51	.295	2	7	.64	76	.004	6	.34	.013	.19	1	1	3.1	<1	5.86	1
RE B 169790	2.0	91	12	196	.2	69	36	190	6.42	74	<1	<2	1	93	.7	3.2	<.5	13	1.56	.297	2	8	.65	79	.006	3	.37	.015	.21	1	2	3.2	<1	6.01	1
B 169791	3.1	102	15	306	.2	70	36	209	10.70	84	1	<2	<1	74	1.4	3.5	<.5	14	1.24	.285	2	7	.45	72	.004	1	.27	.010	.14	1	6	2.9	1	10.56	1
B 169792	1.8	86	10	110	.2	58	46	648	6.90	122	<1	<2	1	54	1.0	1.2	<.5	15	1.23	.297	4	7	.46	67	.005	3	.42	.017	.24	2	4	3.3	1	5.81	1
B 169793	3.1	162	9	287	.2	64	63	389	9.98	41	<1	<2	1	63	1.2	2.9	<.5	14	1.23	.243	2	6	.40	64	.004	3	.35	.020	.16	1	9	3.8	1	9.21	1
B 169794	2.6	162	8	207	.2	59	61	684	10.30	25	<1	<2	<1	57	.6	3.1	<.5	17	1.11	.228	4	5	.65	71	.003	7	.32	.027	.16	1	14	4.1	3	6.54	1
B 169795	1.8	184	4	139	.1	58	52	655	6.86	14	<1	<2	<1	49	.3	1.4	<.5	20	.92	.275	6	6	.56	107	.005	5	.34	.034	.17	1	4	3.7	2	3.11	2
B 169796	1.4	168	2	114	.1	54	48	1033	7.42	13	<1	<2	1	55	<.2	.6	<.5	15	.93	.274	6	5	.93	125	.004	7	.28	.029	.14	<1	<1	5.1	<1	.94	1
B 169797	2.5	192	4	152	.1	52	48	550	5.60	20	<1	<2	1	64	.3	1.8	<.5	14	1.13	.268	5	6	.49	118	.007	6	.34	.031	.16	1	2	4.1	<1	2.77	1
B 169798	1.5	177	4	164	.2	55	46	826	8.02	10	<1	<2	1	43	.2	1.8	<.5	15	.88	.243	5	5	.53	79	.006	6	.32	.030	.16	1	2	4.0	<1	4.71	<1
B 169799	1.2	118	3	174	.1	68	54	1253	8.37	9	<1	<2	1	43	.2	1.3	<.5	13	.87	.298	5	6	.86	131	.005	2	.38	.032	.18	1	2	4.1	1	2.60	1
B 169800	1.2	169	5	125	.2	55	48	1268	7.97	14	<1	<2	<1	51	.3	.7	<.5	15	1.09	.248	4	5	.92	102	.005	2	.29	.025	.12	1	1	5.7	<1	1.92	1
B 169801	1.2	199	3	121	.2	67	60	1412	8.10	19	<1	<2	2	35	<.2	.7	<.5	18	.70	.247	7	4	.86	121	.004	2	.34	.035	.15	<1	1	6.3	<1	1.53	1
B 169802	1.0	143	2	81	.1	53	46	1500	7.23	5	<1	<2	1	47	<.2	<.5	<.5	24	1.07	.261	6	5	1.23	133	.003	2	.32	.030	.12	<1	<1	6.8	<1	.54	1
B 169803	.8	120	<2	76	.1	57	46	1693	7.60	3	<1	<2	2	35	<.2	<.5	<.5	31	.89	.236	8	6	1.23	111	.003	<1	.33	.040	.12	<1	<1	6.0	<1	.26	1
B 169804	.6	125	2	78	.1	55	49	1537	6.81	4	<1	<2	1	38	<.2	<.5	<.5	27	.90	.236	7	6	1.10	112	.003	2	.37	.043	.12	1	<1	5.9	1	.54	1
STANDARD C3	27.9	67	36	174	5.3	38	12	855	3.42	59	24	<2	22	30	23.6	16.5	23.6	85	.63	.097	19	179	.65	166	.095	22	1.83	.045	.18	15	1	4.6	<1	.03	9
STANDARD G-2	1.5	3	3	43	<.1	8	4	567	2.05	<1	2	<2	3	78	<.2	<.5	<.5	41	.67	.104	7	77	.62	251	.130	1	.96	.112	.54	2	<1	2.5	<1	<.01	5

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB

SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns

DATE RECEIVED: OCT 6 2000 DATE REPORT MAILED: Oct 17/00 SIGNED BY .....D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 169805	1.5	69	<2	104	.1	32	29	1872	7.53	3	<1	<2	1	101	.2	<.5	<.5	24	3.16	.142	4	12	1.89	150	.022	4	.47	.030	.16	<1	<1	7.3	<1	.43	1
B 169806	.8	203	2	96	.1	54	46	1642	7.56	4	<1	<2	1	50	<.2	<.5	.6	26	1.28	.203	5	6	1.21	136	.014	4	.40	.052	.15	<1	<1	6.1	3	1.57	2
B 169807	.7	247	2	117	.2	55	49	1431	8.28	9	<1	<2	<1	61	.2	<.5	<.5	20	1.47	.186	3	6	1.59	179	.021	5	.48	.037	.17	<1	<1	6.7	2	1.76	2
B 169808	1.1	193	4	141	.1	77	64	1506	10.88	24	<1	<2	<1	52	<.2	2.5	<.5	21	1.31	.143	2	6	1.34	97	.008	4	.32	.030	.12	1	1	7.5	4	5.76	2
B 169809	2.0	10	4	41	.3	128	48	2637	7.31	292	1	<2	<1	441	.5	1.5	.5	24	12.99	.183	2	27	3.95	70	.028	3	.34	.016	.20	1	<1	11.0	2	1.21	<1
B 169810	.7	5	<2	42	.3	84	35	2373	6.59	134	1	<2	<1	410	.7	.6	<.5	23	13.48	.128	2	9	4.04	61	.015	4	.28	.013	.17	<1	<1	11.4	1	.63	<1
B 169811	.6	16	<2	37	.3	53	34	2386	6.77	95	1	<2	<1	389	.5	<.5	<.5	23	10.40	.178	4	6	3.51	77	.024	3	.40	.021	.22	<1	<1	10.0	<1	.14	<1
B 169812	.5	101	2	106	.1	147	55	1127	7.74	158	<1	<2	1	69	.8	1.2	<.5	13	2.58	.119	2	23	1.69	61	.004	3	.29	.019	.13	<1	<1	7.0	<1	1.10	1
B 169813	.5	122	<2	103	.1	174	56	1293	8.61	28	<1	<2	<1	40	<.2	<.5	<.5	27	1.26	.118	2	47	1.48	99	.005	4	.45	.047	.14	<1	<1	8.8	1	1.21	1
B 169814	.5	92	<2	88	.2	95	42	1557	8.23	2	<1	<2	1	98	<.2	<.5	<.5	73	4.02	.141	4	36	2.06	106	.016	2	1.42	.045	.11	<1	<1	9.4	<1	.18	5
B 169815	.6	138	<2	70	.3	63	34	1454	6.67	3	<1	<2	<1	129	<.2	.7	<.5	58	5.29	.127	3	33	1.98	170	.021	4	1.06	.047	.16	<1	<1	8.4	<1	.55	4
RE B 169815	.7	146	<2	68	.3	60	34	1425	6.84	4	<1	<2	<1	125	<.2	<.5	<.5	56	5.16	.123	3	31	1.94	159	.020	3	1.01	.044	.15	<1	<1	8.4	1	.53	3
B 169816	2.2	172	2	109	.2	52	45	1938	7.71	3	<1	<2	1	60	.2	<.5	<.5	55	1.95	.173	5	8	1.33	88	.017	3	.71	.096	.10	<1	<1	8.8	1	.66	4
B 169817	.9	125	2	75	.2	42	35	1680	7.36	4	<1	<2	<1	114	<.2	<.5	<.5	51	4.90	.151	4	9	1.84	93	.020	1	.86	.104	.10	<1	<1	8.1	<1	.46	3
B 169818	.9	124	3	76	.2	39	40	1644	7.76	4	<1	<2	<1	104	<.2	<.5	<.5	51	4.24	.140	3	12	1.73	119	.032	2	1.18	.118	.13	<1	<1	7.4	1	.77	4
B 169819	1.0	137	3	62	.2	49	40	1805	7.55	3	<1	<2	<1	142	<.2	<.5	<.5	50	6.34	.118	2	13	2.01	107	.031	4	1.19	.106	.12	<1	<1	7.8	<1	1.38	4
STANDARD C3	27.8	67	36	171	5.3	38	13	834	3.29	59	24	2	20	28	25.7	17.5	23.1	81	.61	.095	19	183	.63	162	.092	23	1.85	.046	.17	16	1	4.3	<1	.03	8
STANDARD G-2	1.4	2	3	41	<.1	7	4	542	1.96	<1	2	<2	3	87	<.2	<.5	<.5	40	.71	.097	7	77	.60	246	.130	1	1.10	.160	.56	2	<1	2.5	<1	<.01	5

Sample type: CORE PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A000825R3

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 169602	1.0	45	15	59	.6	99	40	3674	6.49	220	1	<2	1	273	.8	2.4	1.9	15	9.09	.114	2	11	3.53	55	.010	2	.28	.010	.12	1	<1	9.5	1	1.88	1
B 169603	5.9	44	45	49	1.1	158	94	2922	13.15	541	1	9	<1	130	<.2	<.5	7.3	17	5.21	.179	3	7	1.87	71	.021	12	.41	.010	.17	1	<1	8.5	<1	9.34	2
B 169604	3.4	12	25	58	.4	155	57	3382	9.82	377	1	<2	1	227	.3	<.5	5.4	16	8.17	.096	2	20	3.31	107	.014	11	.46	.012	.22	1	<1	10.6	<1	5.42	2
B 169605	7.6	13	39	84	.8	133	77	3418	12.31	454	1	5	<1	151	.3	.9	8.9	16	6.04	.222	3	7	1.94	90	.032	2	.46	.008	.22	6	<1	8.0	<1	8.01	2
B 169606	1.0	10	16	23	<.1	27	5	1127	1.79	53	1	<2	5	90	.2	1.0	<.5	5	2.33	.068	10	10	.86	82	.006	13	.42	.013	.23	1	<1	2.7	<1	.40	1
B 169607	1.0	6	5	16	<.1	39	5	2017	2.82	91	2	<2	4	129	.2	<.5	<.5	8	3.53	.076	8	5	1.24	77	.005	6	.38	.009	.22	1	<1	5.6	<1	.92	1
B 169608	1.0	36	4	22	<.1	27	9	314	2.28	56	2	<2	3	21	<.2	1.8	<.5	3	.53	.032	10	9	.43	99	.002	5	.35	.010	.19	2	<1	1.7	<1	1.07	1
B 169609	.9	18	7	10	<.1	28	12	339	2.05	144	1	<2	2	29	.2	.8	<.5	3	.70	.025	8	10	.26	64	.002	3	.22	.007	.13	3	<1	1.6	<1	1.77	<1
B 169610	1.1	26	20	38	<.1	28	13	336	3.00	136	2	<2	4	44	.3	.6	<.5	5	.76	.041	11	9	.39	138	.004	14	.48	.014	.25	2	<1	2.4	<1	2.31	1
B 169611	5.2	42	20	68	<.1	51	19	609	4.34	110	3	<2	4	25	.2	<.5	<.5	8	.49	.089	9	8	.80	127	.007	11	.40	.012	.20	1	<1	2.2	<1	1.80	1
B 169612	2.6	97	20	122	.2	86	32	175	11.37	166	1	<2	1	53	.5	5.3	.8	15	.94	.255	5	11	.42	77	.013	3	.47	.012	.22	2	10	3.1	1	10.23	1
B 169613	3.8	56	17	56	.3	121	43	317	8.30	266	2	<2	2	74	<.2	7.9	2.7	14	1.05	.190	7	22	.49	87	.010	5	.53	.012	.25	2	20	3.7	3	7.91	1
B 169614	1.9	30	36	63	.7	124	54	102	10.65	364	1	2	1	75	<.2	1.8	9.8	16	.98	.340	6	7	.13	73	.014	3	.49	.017	.23	2	2	3.0	<1	10.27	1
B 169615	1.6	3	3	9	<.1	24	29	69	.91	107	1	<2	2	65	<.2	<.5	<.5	18	.63	.290	11	3	.07	234	.012	7	.53	.010	.25	2	<1	3.2	<1	.73	1
B 169616	2.7	150	17	121	.5	76	50	297	6.17	195	1	3	1	46	.4	1.5	1.5	17	.64	.275	7	5	.31	87	.009	3	.44	.011	.21	2	<1	3.2	<1	6.10	1
B 169617	6.1	154	12	214	.1	90	45	286	11.53	166	1	<2	1	40	.7	1.7	<.5	26	.68	.283	7	11	.39	64	.011	2	.49	.010	.23	2	1	4.2	<1	9.14	1
B 169618	7.3	113	8	97	.1	53	43	511	4.13	181	2	<2	1	60	.4	<.5	<.5	15	.98	.301	8	6	.42	156	.009	5	.44	.010	.22	2	<1	3.4	<1	3.45	1
RE B 169618	7.1	117	8	110	.1	54	46	515	4.15	182	2	<2	1	61	.5	1.0	<.5	17	.99	.308	8	6	.43	160	.010	6	.46	.011	.22	2	<1	3.4	<1	3.29	1
B 169619	3.2	132	7	62	.1	86	48	738	5.77	154	1	<2	1	80	.2	.9	<.5	18	1.70	.186	5	15	.71	132	.014	7	.49	.015	.24	2	1	5.0	1	5.10	1
B 169620	4.6	62	20	50	.1	60	39	694	5.76	222	1	<2	1	118	.3	<.5	1.4	16	1.51	.355	7	6	.58	117	.007	7	.52	.017	.25	3	<1	5.4	<1	5.31	1
B 169621	1.9	38	115	40	5.3	170	92	1177	15.13	628	1	47	2	133	<.2	<.5	13.1	15	2.65	.285	6	5	.75	80	.015	8	.31	.005	.15	2	4	8.3	<1	12.44	1
B 169622	1.8	28	48	32	1.8	136	70	1284	10.92	455	1	12	1	127	<.2	<.5	6.7	12	2.83	.264	6	4	.95	92	.009	2	.28	.005	.13	1	2	7.9	1	9.29	1
B 169623	1.1	15	37	23	.6	44	16	80	6.00	179	2	6	4	17	.2	1.6	2.8	5	.34	.059	8	10	.08	62	.003	8	.41	.006	.21	2	2	1.3	<1	7.13	<1
STANDARD C3	26.7	70	34	168	5.3	36	11	781	3.27	56	23	2	21	28	22.2	16.9	22.8	80	.58	.094	22	174	.60	159	.093	23	1.80	.041	.17	15	1	4.4	1	.03	7
STANDARD G-2	1.5	2	3	41	<.1	7	3	514	1.92	<1	3	<2	5	81	<.2	<.5	<.5	39	.66	.096	10	75	.58	242	.136	<1	1.04	.136	.52	1	<1	2.6	<1	<.01	4

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 6 2000 **DATE REPORT MAILED:** Oct 16/00 **SIGNED BY** ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD File # A001465R

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 169975	6.0	35	9	71	.1	65	17	1563	4.03	115	2	<2	4	228	.3	1.0	<.5	27	5.95	.233	6	15	2.23	134	<.001	5	.44	.017	.19	1	<1	5.8	<1	1.34	1
B 169976	3.2	140	9	112	.2	194	58	1570	7.25	229	4	<2	1	176	.4	3.8	.9	16	6.11	.179	2	18	2.23	79	<.001	1	.42	.015	.09	1	<1	7.6	<1	3.81	1
B 169977	4.2	126	22	140	.3	137	41	1573	6.14	127	<1	<2	<1	169	.5	1.9	<.5	16	7.10	.149	2	18	2.47	99	.001	2	.28	.026	.10	1	<1	7.4	<1	3.58	1
B 169978	1.7	148	6	37	.1	238	56	1248	4.80	299	<1	<2	<1	161	<.2	3.3	<.5	17	6.85	.161	2	29	2.23	148	.001	4	.34	.023	.13	2	<1	7.6	<1	2.32	1
B 169979	10.5	30	43	60	.5	109	35	2650	9.52	110	1	<2	1	341	<.2	<.5	4.5	21	14.11	.053	2	27	6.23	101	<.001	<1	.20	.020	.07	<1	<1	7.7	1	6.95	1
B 169980	9.7	33	44	62	.4	86	44	2272	8.87	108	2	<2	1	400	<.2	<.5	3.5	26	13.09	.206	2	11	4.86	110	.001	3	.35	.014	.13	<1	<1	11.3	2	6.00	1
B 169981	4.9	38	32	49	.5	149	51	2156	9.27	192	1	<2	1	426	<.2	.6	5.1	23	13.05	.169	2	19	4.86	115	.001	2	.36	.014	.13	1	<1	12.2	<1	6.34	<1
B 169982	18.1	48	20	54	.3	114	39	1977	7.06	124	1	<2	1	296	<.2	<.5	2.8	18	12.26	.135	2	14	4.55	107	.001	1	.25	.016	.10	1	<1	8.6	<1	4.67	1
RE B 169982	16.5	49	20	54	.3	117	39	1968	7.07	126	1	<2	1	295	<.2	<.5	2.9	18	12.14	.133	2	14	4.52	106	.001	2	.24	.016	.10	1	<1	8.6	<1	4.64	1

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 6 2000 DATE REPORT MAILED: Oct 14/00 SIGNED BY..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

WHOLE ROCK ICP ANALYSIS

Standard Drilling File # A001248R3

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: R. Hall

SAMPLE#	SiO2 %	Al2O3 %	Fe2O3 %	MgO %	CaO %	Na2O %	K2O %	TiO2 %	P2O5 %	MnO %	Cr2O3 %	Ba ppm	Ni ppm	Sr ppm	Zr ppm	Y ppm	Nb ppm	Sc ppm	LOI %	TOT/C %	TOT/S %	SUM %
B 169908	52.97	12.28	7.30	4.00	8.64	.57	2.46	1.19	.31	.14	.033	1543	127	284	122	22	22	19	9.7	3.66	1.49	99.84
B 169910	44.63	13.22	10.47	4.04	9.03	2.20	1.98	3.05	.50	.17	.019	1448	57	245	164	26	35	26	10.3	3.84	2.77	99.84
B 169912	38.82	12.31	10.26	5.66	13.01	1.17	1.63	2.69	.58	.20	.020	1857	78	262	144	23	33	23	13.2	4.85	2.60	99.83
B 169915	37.21	11.76	8.22	6.67	14.44	.85	1.77	2.10	.34	.18	.033	1912	88	281	111	19	23	22	16.0	5.55	1.66	99.85
B 169918	36.67	13.40	10.16	5.46	14.04	.87	2.93	1.71	.30	.15	.037	2969	117	297	85	17	15	26	13.7	5.37	1.75	99.83
B 169921	44.55	13.65	11.93	3.76	5.89	2.41	2.14	2.26	.27	.13	.022	1269	82	239	144	22	26	24	12.6	3.42	3.68	99.82
B 169924	18.03	14.00	16.04	8.46	17.08	.27	3.32	1.69	.31	.29	.050	2597	211	645	108	25	28	33	15.0	6.78	5.02	94.96
B 169927	38.42	20.56	10.74	2.44	5.19	.43	5.66	4.17	.64	.10	.016	3200	62	246	253	34	60	32	11.1	2.12	5.21	99.91
B 169931	38.01	18.39	13.21	3.75	4.85	.73	4.71	3.39	.73	.22	.015	2881	64	247	225	41	46	28	11.4	3.38	1.91	99.81
B 169935	30.73	23.50	12.34	2.33	5.45	.53	6.27	4.95	.90	.13	.017	2866	73	316	288	42	72	40	12.2	1.92	7.13	99.77
B 169938	35.25	25.80	9.38	2.40	3.80	.59	7.21	4.83	.48	.14	.026	2664	85	222	262	37	59	49	9.6	1.96	3.33	99.90
B 169941	31.18	23.55	12.79	2.88	4.21	.57	6.46	5.04	.69	.21	.017	2509	65	248	288	38	65	39	11.8	2.42	4.76	99.77
B 169944	30.31	23.36	10.51	3.64	7.38	.56	6.34	4.10	.47	.25	.014	3019	89	351	242	37	50	38	12.4	3.30	3.74	99.77
RE B 169944	30.38	23.38	10.65	3.63	7.39	.58	6.33	4.07	.45	.25	.016	3030	97	351	236	38	54	38	12.2	3.23	3.65	99.77
B 169947	27.33	21.33	11.42	4.73	9.29	.57	5.79	4.18	.61	.30	.018	2964	50	480	267	40	63	39	13.8	4.54	2.06	99.82
B 169950	31.16	18.64	16.00	3.26	5.07	1.87	4.22	3.84	.51	.21	.017	2692	90	290	209	31	52	34	14.6	2.97	6.87	99.79
B 169953	18.34	10.31	35.26	2.16	4.64	1.76	1.90	2.34	.46	.10	.021	1460	78	234	131	19	33	19	20.6	1.99	26.30	98.12
B 169956	21.90	14.02	29.76	2.22	4.75	.26	3.93	3.09	.40	.13	.015	2957	<20	196	187	24	41	25	19.0	1.91	23.04	99.87
B 169959	41.98	24.94	10.52	1.73	2.25	.44	6.78	1.29	.26	.06	.027	4229	70	172	352	47	23	22	9.0	.99	7.33	99.84
B 169962	39.42	28.63	6.71	2.83	4.42	.56	8.00	1.25	.20	.13	.024	2407	57	315	286	49	20	26	7.3	2.09	2.65	99.84
B 169965	55.77	19.48	8.86	1.02	.85	.39	5.19	.87	.17	.03	.019	1527	46	122	213	32	18	16	7.1	.60	5.53	99.98
STANDARD SO-15/CSB	49.10	12.82	7.31	7.27	5.88	2.41	1.85	1.66	2.70	1.39	1.061	1951	78	396	912	22	22	12	5.9	2.46	5.48	99.76

GROUP 4A - 0.200 GM SAMPLE BY LIBO2 FUSION, ANALYSIS BY ICP-ES. LOI BY LOSS ON IGNITION.
TOTAL C & S BY LECO. (NOT INCLUDED IN THE SUM)
- SAMPLE TYPE: CORE PULP
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 6 2000 DATE REPORT MAILED: Oct 18/00 SIGNED BY. ..... J. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Standard Drilling File # A001248R2

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: R. Hall

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 169908	2.3	92	3	101	.2	127	49	1146	4.67	21	1	<2	2	189	.6	<.5	.7	15	6.37	.110	2	15	2.21	131	.004	7	.39	.033	.19	<1	<1	5.1	<1	1.48	1
B 169909	2.0	130	4	120	.3	191	57	1512	6.29	18	2	<2	1	219	.6	<.5	.5	24	8.33	.162	1	41	2.84	149	.012	7	.53	.050	.23	1	<1	8.3	<1	1.99	1
B 169910	3.9	119	7	72	.4	55	36	1377	6.64	8	<1	<2	1	153	<.2	1.1	.9	21	6.87	.190	1	6	2.21	103	.009	4	.41	.038	.13	1	<1	7.4	<1	3.06	1
B 169911	4.0	238	104	58	.7	53	36	1390	6.18	26	1	<2	2	155	<.2	.8	.7	20	7.92	.230	1	6	2.59	108	.010	5	.58	.028	.13	1	<1	6.6	<1	3.08	2
B 169912	3.3	73	7	68	.3	66	34	1591	6.44	67	1	<2	1	190	.4	<.5	<.5	16	8.99	.201	1	7	3.09	118	.010	4	.56	.023	.11	39	<1	7.5	<1	2.99	1
B 169913	2.3	43	5	60	.2	96	32	1443	5.51	102	1	<2	1	222	.4	<.5	1.4	18	9.68	.182	2	12	3.38	142	.008	3	.45	.020	.12	1	<1	7.2	<1	1.60	1
B 169914	1.9	58	3	55	.2	82	29	1742	4.69	76	2	<2	1	197	.4	2.0	<.5	18	9.95	.160	1	12	3.43	136	.008	3	.40	.019	.09	1	<1	8.0	<1	.97	<1
B 169915	3.2	77	4	66	.4	89	34	1402	4.85	61	1	<2	1	180	.3	7.9	<.5	21	9.79	.117	1	15	3.64	136	.009	5	.41	.027	.12	1	<1	8.2	<1	1.56	<1
RE B 169915	3.2	77	4	67	.4	90	35	1408	4.79	60	1	<2	2	180	.4	6.9	<.5	20	9.79	.118	1	15	3.64	138	.008	5	.41	.027	.13	1	<1	8.2	<1	1.59	<1
B 169916	1.9	109	4	123	.2	210	47	1010	6.34	43	1	<2	<1	193	.2	<.5	<.5	16	7.50	.060	<1	33	3.86	140	.002	5	.33	.033	.15	<1	<1	8.9	<1	.99	1
B 169917	2.5	58	33	71	.4	146	38	1241	4.80	157	2	<2	1	261	.9	<.5	<.5	12	11.73	.056	1	17	3.01	128	.002	6	.28	.018	.14	1	<1	7.9	<1	1.02	<1
B 169918	4.2	76	8	65	.3	122	39	1207	6.33	97	1	<2	<1	240	.5	<.5	.5	18	9.66	.117	1	17	2.98	185	.006	7	.38	.021	.19	<1	<1	7.5	<1	1.70	1
B 169919	3.6	128	10	123	.3	62	41	1204	8.33	16	<1	<2	<1	202	<.2	.8	<.5	28	6.25	.153	2	8	2.05	151	.005	3	.44	.034	.16	1	<1	7.7	<1	4.75	2
STANDARD C3	26.5	68	34	170	5.3	36	12	801	3.21	56	23	<2	21	28	24.4	16.8	22.3	79	.59	.093	17	168	.61	154	.092	23	1.86	.043	.17	18	1	4.3	<1	.03	9
STANDARD G-2	1.5	2	2	43	<.1	8	4	534	1.96	<1	3	<2	4	75	<.2	<.5	<.5	42	.65	.099	6	76	.60	238	.137	3	1.01	.108	.52	2	<1	2.5	<1	<.01	6

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 6 2000 DATE REPORT MAILED: Oct 16/00 SIGNED BY: .....D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A001248R Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	Al %	Na %	K %	W ppm	Zr ppm	Ce ppm	Sn ppm	Y ppm	Nb ppm	Ta ppm	Be ppm	Sc ppm	Li ppm	S %	Rb ppm	Hf ppm
B 169920	2.9	118	13	116	<.2	89	35	1168	8.80	<2	<1	<4	5	211	.3	1	<1	202	4.11	.109	12	114	2.24	354	.190	7.21	1.818	1.67	2	36.4	27	<.5	6.1	3.6	<.5	1	26	43	2.46	84	1
B 169921	2.6	107	12	98	<.2	84	34	1017	8.61	<2	<1	<4	3	219	<.2	2	<1	197	4.25	.118	14	115	2.11	444	.206	7.35	1.860	1.71	3	41.5	31	<.5	5.3	3.3	<.5	1	26	42	2.81	88	1
B 169922	2.4	28	11	82	< 2	33	13	442	4.09	<2	4	<4	12	102	<.2	1	<1	75	.50	.034	31	57	.99	1251	.088	7.12	.288	2.40	2	75.9	59	2.1	5.6	<.2	<.5	2	12	54	.50	110	2
B 169923	1.2	11	13	49	.3	59	25	1314	6.62	16	5	<4	105	399	<.2	4	4	163	6.59	.134	49	136	2.58	934	.205	10.50	.346	3.98	6	95.6	100	2.9	12.7	5.6	<.5	4	22	15	2.71	220	3
B 169924	1.2	7	10	73	.3	126	47	1962	9.65	27	<1	<4	3	527	.4	<1	1	184	10.15	.112	12	188	4.34	577	.142	6.34	.200	2.35	4	38.8	29	<.5	10.1	1.2	<.5	2	30	10	3.29	149	1
B 169925	1.8	71	10	164	<.2	41	26	409	5.50	5	3	<4	1	162	.7	4	<1	209	2.92	.233	19	54	1.08	641	.273	7.08	.210	2.63	6	42.3	43	.5	7.5	5.3	<.5	2	21	10	2.70	130	1
B 169926	1.2	85	6	64	<.2	43	26	1374	6.34	7	<1	<4	5	272	.2	2	<1	259	5.72	.140	14	55	2.26	803	.422	6.94	.770	2.34	6	26.8	28	<.5	5.8	9.4	<.5	2	26	8	1.10	126	1
B 169927	.5	14	10	34	<.2	75	62	766	7.71	10	<1	<4	4	212	<.2	3	5	324	3.94	.263	14	61	1.35	605	.417	10.25	.296	3.89	11	41.8	34	2.5	10.7	7.5	<.5	3	32	11	3.83	253	1
B 169928	1.2	26	12	29	<.2	132	105	264	10.07	16	2	<4	2	156	<.2	3	8	450	1.94	.412	6	64	.55	252	.421	12.22	.338	5.03	14	33.5	20	5.6	12.5	4.9	<.5	5	39	11	8.16	349	1
B 169929	2.2	<1	7	28	<.2	70	46	1013	6.34	15	<1	<4	3	288	<.2	5	4	379	4.41	.291	13	96	1.51	572	.404	11.57	.344	4.58	10	33.6	34	2.4	12.2	8.7	.5	4	38	12	2.90	289	1
B 169930	.9	4	5	42	<.2	43	40	1016	6.91	19	2	<4	3	185	<.2	2	2	274	2.65	.387	12	65	1.34	766	.369	11.18	.367	4.67	10	32.2	25	3.1	11.3	7.6	<.5	4	28	12	1.91	255	1
B 169931	<.5	37	6	80	<.2	48	39	1615	9.03	19	<1	<4	1	212	.3	1	<1	276	3.51	.274	15	46	2.02	942	.295	8.90	.490	3.02	7	52.2	35	1.6	10.5	6.9	.5	3	27	10	1.57	159	2
B 169932	1.1	24	5	60	<.2	58	46	1474	9.04	30	2	<4	3	148	.6	<1	<1	309	2.15	.287	11	63	1.60	715	.336	9.65	.359	3.85	9	30.8	28	2.0	8.3	5.5	<.5	4	30	11	1.58	201	1
B 169933	.6	18	6	59	<.2	60	49	1873	9.58	34	<1	<4	3	241	<.2	1	2	400	3.75	.263	14	46	1.90	707	.436	10.18	.372	4.00	12	51.3	35	3.4	11.3	8.1	<.5	4	34	10	2.11	207	2
B 169934	.7	16	5	54	<.2	86	63	1298	7.72	48	1	<4	4	222	<.2	3	1	398	3.30	.316	14	57	1.54	522	.428	11.06	.403	4.29	10	43.8	37	3.6	12.2	10.5	.5	4	35	11	2.36	269	1
B 169935	.6	12	22	32	1.1	94	72	1019	10.34	35	1	12	5	267	.2	3	5	409	4.29	.343	20	61	1.30	524	.418	11.27	.352	4.34	12	60.5	51	4.6	16.1	7.3	<.5	4	40	9	7.24	338	2
B 169936	1.6	4	13	29	.5	68	61	824	6.85	12	2	6	1	210	<.2	4	3	324	2.73	.362	8	78	1.00	443	.358	13.08	.455	5.38	12	34.4	22	5.3	12.3	7.6	.8	5	34	12	3.42	355	1
B 169937	6.9	<1	4	38	<.2	43	35	1515	4.41	31	4	<4	4	333	.2	6	2	443	4.71	.205	21	46	1.80	3046	.521	12.30	.467	5.12	12	125.5	51	3.3	15.5	13.2	1.0	4	52	13	.45	308	4
B 169938	.8	13	9	42	<.2	116	69	3125	7.31	30	1	<4	1	185	<.2	5	1	436	2.89	.169	9	117	1.33	472	.334	12.46	.427	5.17	11	38.3	24	4.9	8.5	7.3	.9	5	48	10	2.87	354	2
B 169939	.6	16	15	30	.3	101	79	847	9.13	26	<1	4	2	221	<.2	3	3	416	3.56	.206	7	46	1.22	328	.451	12.04	.421	4.91	14	29.9	22	3.9	10.3	6.5	<.5	4	48	11	5.08	349	1
B 169940	9	17	14	35	.2	89	65	1196	8.18	66	<1	<4	3	258	.2	2	2	389	4.22	.206	10	57	1.50	450	.486	10.93	.400	4.40	14	38.1	26	3.7	10.8	10.2	<.5	4	41	10	4.01	270	2
RE B 169940	.9	17	13	34	.2	87	64	1165	7.90	34	<1	<4	3	252	<.2	5	2	389	4.16	.208	13	60	1.50	483	.508	10.88	.397	4.37	14	40.3	35	4.3	10.9	11.2	<.5	4	41	10	3.96	266	1
RRE B 169940	.9	16	14	34	.3	90	62	1167	8.16	37	<1	<4	3	252	<.2	3	1	381	4.17	.212	12	59	1.52	460	.503	10.92	.396	4.32	14	39.8	30	3.7	11.3	11.6	.7	4	41	10	4.09	289	1
B 169941	.7	13	18	48	.6	84	66	1673	10.29	54	1	7	1	210	<.2	2	1	391	3.39	.256	12	60	1.65	398	.433	10.64	.385	4.20	13	38.4	29	3.9	11.1	7.7	<.5	3	36	9	4.12	278	1
B 169942	1.5	39	17	48	.4	65	44	1698	9.38	53	<1	<4	1	207	<.2	2	<1	361	3.37	.210	11	69	1.69	451	.424	10.82	.398	4.36	13	38.8	29	4.3	10.2	10.3	.5	4	34	10	3.71	256	1
B 169943	1.1	216	15	43	.4	55	38	2109	6.75	47	<1	<4	2	334	<.2	5	1	352	6.60	.182	17	48	2.36	1055	.461	10.51	.362	4.14	13	71.9	39	7.0	13.3	10.0	<.5	4	34	11	2.24	241	2
B 169944	1.2	53	9	37	.2	109	79	1879	7.83	23	<1	<4	3	303	<.2	4	1	355	5.43	.164	13	45	2.03	483	.333	11.35	.381	4.43	10	37.2	32	4.5	11.5	7.3	<.5	4	37	11	2.91	308	1
B 169945	1.0	8	3	66	<.2	62	55	2087	9.87	32	<1	<4	<1	309	.3	3	1	385	5.05	.222	11	36	2.42	1785	.398	9.90	.572	3.53	9	53.8	28	1.0	11.5	8.3	<.5	3	40	9	1.05	253	2
B 169946	1.2	2	4	54	<.2	56	44	2054	8.06	29	<1	<4	3	436	.2	2	<1	411	6.82	.275	17	29	2.57	1704	.383	9.46	.349	3.65	9	75.0	41	1.6	14.6	11.3	.5	3	37	8	1.04	211	2
B 169947	.6	6	6	48	<.2	52	40	2110	8.11	29	<1	<4	2	401	<.2	4	<1	345	6.22	.205	15	46	2.53	1025	.425	9.74	.370	3.64	11	68.6	35	2.8	14.0	11.9	<.5	3	37	9	1.74	246	2
B 169948	1.1	11	27	51	<.2	101	56	2008	8.21	51	<1	<4	1	455	<.2	4	<1	415	7.19	.268	14	110	2.60	805	.419	9.60	.326	3.69	15	55.9	36	2.1	15.7	8.1	<.5	4	49	9	2.38	264	2
B 169949	1.9	102	58	82	1.1	82	55	1138	26.80	25	<1	<4	3	233	<.2	9	10	155	4.82	.081	10	14	1.55	275	.130	3.86	.147	1.51	5	27.3	24	.7	7.6	3.5	<.5	1	21	4	24.81	101	1
B 169950	3.2	17	9	65	<.2	98	62	1631	12.17	24	<1	<4	3	242	<.2	2	<1	356	3.93	.217	9	36	1.87	685	.332	9.03	1.308	2.82	9	50.2	26	1.3	10.5	4.2	<.5	3	34	8	4.69	211	1
STANDARD CT3	27.1	61	39	177	5.7	38	12	979	4.37	60	27	<4	26	230	19.6	21	21	138	1.57	.095	25	265	.93	1084	.376	7.11	1.880	1.73	26	45.1	45	19.0	12.6	16.3	<.5	5	11	33	.03	75	1
STANDARD G-2	1.8	<1	21	50	<.2	7	4	775	2.69	2	5	<4	8	774	<.2	4	1	59	3.08	.091	25	71	.72	1020	.263	8.28	2.684	2.64	2	8.2	45	.9	12.9	16.6	1.4	3	7	34	<.01	124	1

GROUP 1EX - 0.25 GM SAMPLE DIGESTED WITH HCLO4-HNO3-HCL-HF TO 10 ML. UPPER LIMITS - AG, AU, U = 200 PPM; MO, CO, CD, SB, BI, TH & U = 4,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM. DIGESTION IS PARTIAL FOR SOME MINERALS & MAY VOLATIZE SOME ELEMENTS, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE REJ. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUL 20 2000 DATE REPORT MAILED: July 31/00 SIGNED BY: ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	Al %	Na %	K %	W ppm	Zr ppm	Ce ppm	Sn ppm	Y ppm	Nb ppm	Ta ppm	Be ppm	Sc ppm	Li ppm	S %	Rb ppm	Hf ppm
B 169951	2.1	17	8	75	<.2	88	61	1976	12.04	22	1	<4	<1	249	.4	1	5	406	3.81	.249	15	42	2.08	307	.438	10.26	.685	3.37	13	31.8	38	3.5	10.7	8.9	<.5	4	37	11	4.31	264	1
B 169952	10.6	99	66	75	1.5	87	53	691	20.45	22	1	7	2	156	<.2	35	17	113	3.11	.074	10	30	1.09	100	.117	3.00	.713	.93	3	16.1	21	1.7	4.2	<.2	<.5	1	11	3	28.27	53	2
B 169953	4.2	108	36	73	1.1	103	72	787	22.58	15	3	<4	3	159	.4	7	13	235	3.14	.130	9	27	1.11	109	.168	5.74	1.259	1.67	6	22.4	24	5.2	5.9	4.2	<.5	1	22	6	21.48	113	1
B 169954	2.1	13	3	78	<.2	70	43	1744	9.64	19	<1	<4	3	232	.4	4	2	323	3.63	.222	12	34	2.07	360	.373	9.84	1.878	2.85	8	28.5	32	1.6	8.0	8.9	<.5	2	33	9	2.46	200	1
B 169955	2.4	25	5	49	<.2	53	21	1902	6.45	21	<1	<4	1	273	<.2	4	1	379	5.34	.242	10	50	2.04	624	.503	11.08	.317	4.16	12	29.1	27	3.5	11.9	11.1	<.5	3	38	13	1.60	254	1
B 169956	4.4	152	18	53	.5	69	100	1095	19.84	33	2	<4	<1	127	<.2	5	5	228	3.51	.147	6	28	1.24	148	.180	6.76	.171	2.55	6	26.2	20	4.2	8.1	5.1	<.5	2	24	8	19.50	176	1
B 169957	3.2	2	7	34	<.2	34	18	1435	4.67	18	4	<4	2	236	<.2	6	2	359	4.98	.275	23	61	1.84	611	.493	11.84	.311	4.61	10	90.5	50	4.8	14.0	10.9	<.5	4	33	16	2.03	322	3
B 169958	4.3	14	9	28	<.2	47	24	299	5.35	15	9	<4	13	110	<.2	7	5	176	.85	.085	29	117	.66	540	.171	13.94	.325	5.26	7	175.6	71	12.0	8.9	.7	<.5	6	23	17	3.85	404	6
B 169959	3.7	30	12	39	<.2	62	29	510	7.67	15	8	<4	10	125	.4	5	4	146	1.57	.083	21	137	.88	213	.143	12.12	.276	4.61	6	148.0	60	6.2	9.0	<.2	<.5	5	23	16	4.99	353	5
B 169960	4.7	51	17	54	.3	140	46	207	11.00	31	7	<4	6	87	.5	8	7	177	.66	.076	13	230	.54	216	.135	12.84	.317	4.81	4	167.5	47	5.3	8.9	<.2	1.1	5	27	17	9.66	392	5
B 169961	1.5	28	11	27	<.2	54	18	110	3.65	17	5	<4	11	58	<.2	3	<1	92	.27	.036	29	72	.29	215	.091	7.37	.191	2.91	4	82.4	59	2.2	5.0	<.2	<.5	3	15	8	2.89	165	3
RE B 169961	1.8	32	11	24	<.2	53	18	117	3.60	20	5	<4	13	56	<.2	3	<1	90	.26	.038	28	67	.29	176	.088	7.22	.187	2.84	4	82.4	57	2.0	5.0	<.2	.5	3	14	8	2.92	169	2
RRE B 169961	1.6	29	12	29	<.2	56	18	107	3.50	21	5	<4	13	56	<.2	3	<1	90	.26	.039	30	69	.28	228	.090	7.20	.186	2.82	4	81.7	60	1.6	5.2	<.2	<.5	3	14	8	2.88	168	2
B 169962	2.9	14	11	32	<.2	46	18	956	4.59	23	8	<4	19	247	<.2	6	1	148	2.97	.070	50	106	1.35	952	.155	12.59	.327	4.99	4	120.8	98	5.5	10.7	2.7	<.5	4	24	14	2.33	358	4
B 169963	3.1	19	5	22	<.2	41	24	257	6.78	24	7	<4	11	115	<.2	6	2	151	.83	.064	18	91	.62	207	.153	13.87	.381	5.40	6	158.3	54	6.4	7.3	<.2	<.5	5	21	18	4.66	407	5
B 169964	3.6	26	17	39	<.2	74	27	462	6.70	40	7	<4	14	134	.2	5	1	133	1.11	.060	32	113	.80	191	.126	11.67	.299	4.37	4	114.8	68	3.8	8.1	<.2	<.5	4	22	15	4.19	328	4
B 169965	2.3	18	9	34	<.2	60	22	288	6.51	20	6	<4	13	104	<.2	5	1	111	.62	.053	30	109	.56	213	.119	10.13	.256	3.75	5	109.0	66	3.3	7.2	<.2	<.5	3	18	14	4.42	287	3
STANDARD CT3	26.3	61	38	176	5.6	39	10	961	3.97	59	25	<4	24	225	20.1	21	20	130	1.56	.090	26	255	.91	1022	.370	6.88	1.814	1.75	29	48.2	46	19.1	12.9	17.6	<.5	5	11	34	.03	76	1
STANDARD G-2	2.4	<1	20	48	<.2	13	3	752	2.54	2	7	<4	7	733	<.2	1	<1	57	2.94	.088	21	80	.70	1015	.244	7.94	2.567	2.62	2	7.3	38	.6	12.5	16.3	<.5	3	7	34	.02	128	<1

Sample type: CORE REJ Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002493R Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0493	3.1	99	6	42	<.1	52	28	167	4.54	202	1	<2	<1	35	1.1	<.5	2.3	11	.52	.226	5	17	.08	42	.001	6	.49	.015	.24	5	<1	2.0	<1	4.43	1
0494	4.2	13	5	10	<.1	29	13	29	2.88	73	1	<2	3	12	.3	.5	3.7	3	.06	.023	8	19	.01	90	<.001	3	.27	.012	.17	1	1	.6	<1	3.11	<1
0495	1.9	22	12	27	.1	44	14	30	6.36	97	1	<2	3	7	.3	4.4	2.4	4	.08	.030	9	13	.01	38	.001	3	.34	.010	.19	4	5	.6	2	7.09	1
0496	6.4	17	8	14	.3	47	5	32	2.03	112	1	<2	1	55	.3	.5	7.3	19	.32	.163	4	26	.01	76	.001	5	.22	.006	.11	2	<1	.9	<1	1.69	<1
0497	2.4	41	7	72	.1	43	20	174	4.30	165	1	<2	2	47	.9	1.2	1.1	14	.36	.158	6	19	.06	58	.001	3	.36	.009	.16	6	1	1.5	1	4.13	<1
0498	3.6	61	6	141	.2	58	21	1061	4.46	291	1	<2	2	141	.6	7.2	.6	9	2.30	.053	5	16	1.02	81	.001	4	.36	.012	.19	1	<1	3.6	<1	1.68	<1
0499	.6	36	9	100	.1	38	16	781	3.81	362	1	<2	4	186	.7	<.5	<.5	6	2.16	.049	5	12	.91	77	.001	6	.34	.011	.20	5	<1	3.2	<1	2.42	1
0500	3.3	15	6	66	.1	28	13	917	2.93	56	1	<2	5	140	.9	<.5	<.5	3	2.95	.039	8	14	1.31	101	.001	2	.35	.011	.21	1	<1	2.2	<1	.46	1
0501	1.5	141	10	91	.2	104	70	1197	7.15	249	1	<2	1	132	.7	<.5	.6	22	.80	.314	6	8	.55	62	.002	5	.80	.015	.32	2	<1	6.0	<1	3.06	2
0502	2.7	129	7	151	.2	120	65	2211	9.41	264	1	<2	1	64	.8	<.5	<.5	15	.72	.182	4	12	1.61	120	.001	3	.90	.022	.24	<1	1	6.4	1	2.64	2
0503	2.5	193	4	141	.1	96	50	1359	6.92	109	1	<2	<1	35	1.1	<.5	<.5	13	.60	.183	5	12	.90	130	.001	4	.73	.031	.22	1	<1	3.8	<1	2.26	2
0504	1.2	248	4	151	.1	88	63	1487	10.02	97	<1	<2	1	42	1.0	1.3	<.5	18	.86	.196	4	8	1.44	48	.001	3	1.04	.030	.21	1	2	4.7	1	4.83	1
0505	3.6	222	9	123	.2	91	54	1544	9.98	179	<1	<2	<1	71	1.6	.5	.9	17	1.71	.204	4	11	1.48	48	.002	3	1.00	.018	.22	1	2	4.7	2	5.47	1
RE 0505	3.7	221	9	123	.3	92	54	1524	9.65	177	<1	<2	1	71	1.7	<.5	1.1	17	1.69	.205	4	11	1.44	49	.002	4	.97	.018	.22	1	2	4.7	<1	5.41	2
0506	.9	145	5	115	.1	100	48	1215	7.06	164	1	<2	<1	61	1.2	.7	.9	17	1.58	.145	2	12	.98	43	.002	3	.75	.017	.24	3	1	4.5	3	4.58	1
0507	2.8	149	3	74	.1	120	61	1520	6.57	211	1	<2	1	63	1.3	.7	1.1	15	1.24	.164	3	14	1.06	50	.002	3	.60	.017	.23	1	<1	4.6	1	2.54	2
0508	1.0	168	5	139	.2	103	64	1294	5.98	200	1	<2	<1	78	1.9	<.5	<.5	16	1.74	.130	2	19	1.15	59	.002	4	.63	.015	.25	2	<1	5.4	1	2.96	2
0509	4.4	143	3	57	.1	154	48	812	5.37	157	1	<2	<1	67	1.2	<.5	1.3	22	1.90	.212	2	24	1.13	65	.003	5	.65	.015	.27	1	1	5.4	<1	3.26	1
0510	1.3	31	7	50	<.1	36	14	142	5.57	72	1	<2	4	11	.5	1.7	1.4	2	.23	.031	8	13	.11	29	.001	4	.35	.011	.19	5	3	1.0	1	5.81	1
0613	2.9	8	5	57	.2	23	12	1900	6.55	112	2	<2	10	443	.9	<.5	<.5	6	7.43	.099	5	9	3.41	75	<.001	5	.63	.011	.22	1	<1	6.1	<1	1.18	1
0614	.3	25	42	68	.1	31	12	887	3.48	32	1	<2	4	139	.2	<.5	<.5	4	3.99	.031	7	10	1.85	58	<.001	2	.35	.015	.19	3	<1	2.5	<1	.44	1
0615	5.1	18	9	36	<.1	41	14	81	5.94	83	1	<2	3	12	.5	2.4	1.7	2	.23	.036	8	19	.07	37	.001	1	.35	.010	.19	1	4	.7	<1	6.25	<1
0616	1.0	18	9	201	<.1	31	11	92	5.69	85	1	<2	3	12	.9	2.5	.6	2	.22	.025	7	14	.07	36	<.001	3	.31	.010	.17	5	3	.7	<1	6.25	<1
0617	.8	21	11	26	.1	36	15	74	4.73	102	1	<2	4	12	.4	.7	4.5	3	.18	.047	8	14	.04	48	.001	1	.33	.010	.18	5	1	.8	1	5.25	<1
0618	6.4	17	11	23	.1	41	15	72	6.83	114	<1	<2	3	9	.4	2.1	4.6	3	.15	.031	8	21	.04	36	<.001	3	.35	.010	.17	1	5	.6	2	7.25	<1
0619	.8	14	10	27	<.1	30	12	47	4.33	59	1	<2	4	9	.2	1.6	2.6	3	.11	.032	9	13	.02	42	<.001	4	.33	.010	.19	4	3	.6	<1	5.07	<1
0620	4.9	31	33	39	.7	93	38	413	8.77	178	2	<2	8	95	.7	.6	6.7	9	1.23	.111	6	14	.58	29	.001	4	.71	.012	.24	1	2	3.7	1	8.87	2
0621	8.7	55	63	46	1.7	223	128	769	16.38	299	1	<2	<1	199	<.2	3.5	9.6	27	2.16	.297	4	30	1.95	32	.002	5	1.25	.015	.25	4	18	7.3	7	15.61	2
0622	5.8	41	27	47	.7	174	86	661	8.52	258	1	<2	2	156	<.2	1.1	5.4	14	2.24	.194	3	19	1.17	28	.001	5	.76	.012	.25	1	3	6.0	3	7.92	2
0623	6.3	59	34	42	.9	169	86	732	11.07	390	<1	<2	1	179	.2	.7	5.4	26	2.59	.333	4	23	1.45	34	.001	3	1.11	.014	.28	2	3	9.5	2	9.37	1
0624	5.9	27	17	60	.6	82	43	702	9.30	235	1	<2	5	200	1.1	.6	3.8	19	2.75	.285	5	11	1.33	33	.001	7	.96	.013	.30	1	1	6.6	1	7.59	2
0625	6.1	81	63	149	1.6	122	69	145	16.83	300	<1	<2	1	100	.5	4.1	11.9	23	1.08	.381	3	9	.34	25	.002	7	1.20	.010	.27	4	4	4.1	4	17.90	1
0626	6.0	53	44	106	.9	97	65	115	14.63	257	<1	<2	1	98	.3	1.6	8.9	20	1.08	.366	4	10	.26	39	.002	10	1.27	.013	.32	2	4	3.7	7	15.25	1
0627	4.5	42	49	98	1.0	87	64	206	15.45	305	1	<2	<1	116	.3	.9	11.5	23	1.36	.400	3	7	.46	46	.003	14	1.42	.013	.33	2	3	4.0	4	16.87	1
0628	4.2	60	33	85	.6	102	74	55	11.87	235	<1	<2	<1	57	1.2	.5	6.3	21	.79	.325	6	11	.06	50	.002	12	1.06	.014	.32	1	3	2.1	6	12.53	1
STANDARD C3	26.1	70	35	168	5.4	37	12	815	3.36	57	23	<2	19	27	24.6	14.6	22.6	78	.59	.094	18	173	.61	156	.085	20	1.84	.041	.17	16	1	4.2	<1	.03	8
STANDARD G-2	1.4	2	2	93	<.1	7	4	555	1.97	<1	2	<2	3	69	<.2	<.5	<.5	10	.64	.098	7	75	.59	226	.126	1	.95	.086	.50	2	<1	2.6	<1	<.01	5

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 6 2000 DATE REPORT MAILED: Oct 16/00 SIGNED BY. . . . . D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0629	5.1	58	13	148	.2	64	55	105	8.73	179	<1	<2	1	51	1.3	2.2	3.1	21	.85	.348	4	10	.16	31	.002	2	.58	.014	.31	3	2	2.9	4	8.73	2
0630	10.3	46	19	89	.5	127	56	641	9.24	251	4	<2	<1	115	.6	2.7	5.9	35	2.10	.333	2	24	.65	42	.002	<1	.53	.012	.29	1	1	5.7	2	8.65	2
0631	6.6	56	91	81	2.0	120	45	618	15.38	485	2	<2	3	74	.3	6.3	10.6	15	1.29	.198	4	15	.50	33	.001	10	.46	.011	.26	1	8	4.8	5	15.98	2
0632	2.8	32	52	60	.9	87	31	286	12.77	343	2	<2	3	51	<.2	4.9	8.7	9	.67	.092	4	8	.21	30	.001	4	.45	.012	.27	1	8	2.4	6	13.26	1
RE 0632	2.8	31	52	61	.8	87	30	289	12.59	343	2	<2	3	51	<.2	4.6	8.9	9	.67	.092	4	8	.21	30	.001	6	.45	.012	.28	1	8	2.6	7	13.42	1
STANDARD C3	27.5	67	36	167	5.4	38	12	817	3.44	58	24	<2	19	30	25.6	15.6	23.2	83	.63	.102	19	183	.64	168	.093	23	1.87	.044	.18	15	1	4.6	<1	.04	8
STANDARD G-2	1.6	2	2	43	<.1	7	4	529	2.03	1	2	<2	3	72	<.2	<.5	<.5	41	.66	.105	8	76	.60	231	.132	5	.92	.081	.50	2	<1	2.5	<1	<.01	5

Sample type: CORE PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ____

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A001913R

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0361	3.1	70	11	66	.2	119	35	1096	6.31	53	<1	<2	1	216	<.2	3.0	.6	12	8.30	.083	2	12	2.94	113	<.001	5	.30	.013	.12	1	<1	8.6	<1	1.30	1
0362	4.0	121	14	98	.3	66	45	1365	9.00	28	<1	<2	1	166	<.2	2.1	.7	16	6.08	.168	3	8	1.88	51	.001	2	.48	.013	.13	1	<1	7.4	<1	4.31	1
0363	1.4	105	10	78	.2	105	36	1329	7.26	47	1	<2	1	270	<.2	11.3	.5	18	7.49	.095	2	12	2.83	95	.001	2	.27	.014	.12	2	<1	8.5	<1	2.40	1
0364	2.3	89	17	105	.3	75	32	248	12.39	74	3	<2	1	71	<.2	3.5	.7	19	1.61	.304	5	10	.51	39	.002	2	.50	.017	.22	2	5	3.3	1	10.84	<1
0365	1.4	103	18	159	.3	67	28	264	13.92	65	1	<2	1	50	.3	4.2	.5	16	1.22	.206	5	7	.45	37	.002	1	.35	.011	.16	3	11	2.9	2	12.01	<1
0366	2.9	86	11	222	.2	66	40	99	8.11	32	1	<2	1	34	.6	1.8	<.5	17	.65	.234	6	10	.17	34	.002	1	.43	.014	.20	3	5	2.5	2	7.31	<1
0367	1.8	92	5	84	.2	45	30	385	6.22	4	2	<2	1	43	<.2	<.5	<.5	15	.69	.246	7	8	.60	66	.001	2	.37	.012	.18	2	<1	2.9	<1	3.45	1
0368	3.3	148	6	170	.1	55	30	305	6.49	12	2	<2	1	30	.4	<.5	<.5	15	.55	.173	7	9	.47	59	.001	<1	.40	.013	.19	3	<1	3.0	<1	3.34	<1
0369	1.5	72	6	94	.1	66	29	408	5.26	72	1	<2	1	79	.2	.6	1.1	11	1.64	.185	5	11	.68	78	.001	1	.36	.014	.18	3	<1	3.2	<1	3.20	<1
0370	1.3	52	7	81	.1	55	26	335	5.47	61	2	<2	2	67	<.2	1.0	1.8	10	1.48	.155	7	10	.82	52	.001	1	.43	.019	.21	3	1	2.7	<1	3.62	1
0371	1.4	161	8	163	.2	70	48	444	9.39	24	1	<2	1	32	.3	1.2	<.5	18	.56	.220	6	7	.44	37	.002	<1	.40	.013	.18	1	2	3.5	2	6.67	<1
0374	1.3	165	7	184	.2	51	38	248	4.49	9	1	<2	1	49	.2	.6	<.5	20	.80	.280	8	6	.32	83	.001	2	.45	.021	.21	1	<1	3.4	<1	2.54	<1
0375	1.7	176	6	105	.1	56	47	812	6.07	12	1	<2	1	52	.2	1.0	<.5	21	.94	.245	9	8	.55	69	.002	4	.50	.030	.21	1	2	4.4	1	2.72	1
RE 0375	1.5	168	5	99	.1	55	47	807	6.02	13	1	<2	1	52	<.2	.6	<.5	20	.93	.239	9	7	.55	70	.002	4	.49	.029	.20	1	2	4.3	1	2.64	1
0376	1.1	155	7	154	.1	68	52	1038	8.92	20	1	<2	1	42	.3	.5	<.5	26	.94	.237	9	7	.63	41	.002	<1	.39	.045	.15	1	2	4.6	1	4.94	1
0377	1.2	172	5	169	.1	57	46	1407	8.40	10	1	<2	1	41	.2	<.5	<.5	30	.92	.222	9	7	.78	69	.002	<1	.42	.050	.15	1	<1	6.1	1	2.64	1
0378	.5	137	6	85	.1	132	60	759	7.49	20	1	<2	1	53	<.2	1.0	<.5	19	1.35	.147	6	17	.76	55	.001	<1	.45	.036	.16	1	1	5.0	1	3.87	1
0379	1.3	133	6	89	.1	66	48	1120	9.06	30	1	<2	1	66	<.2	1.3	<.5	23	1.71	.168	6	12	.93	58	.002	<1	.50	.056	.17	1	1	5.3	3	4.77	1
0380	1.4	140	5	165	.1	63	48	1299	11.20	42	1	<2	2	51	.2	1.8	.7	22	1.30	.186	6	7	.86	56	.001	<1	.40	.055	.13	2	1	5.0	3	6.56	1
0381	.9	150	5	81	.1	76	52	915	8.66	25	1	<2	1	44	<.2	1.1	.5	28	1.15	.218	6	7	.79	42	.002	1	.40	.051	.14	1	1	6.1	3	4.57	1
0382	1.8	163	8	113	.2	58	57	1004	11.72	46	1	<2	1	67	<.2	<.5	.6	30	2.04	.163	6	8	.99	62	.001	3	.41	.052	.13	2	2	6.3	2	7.90	1
0383	1.1	117	5	115	.1	55	48	1068	9.05	39	1	<2	1	67	<.2	.9	<.5	25	2.04	.201	6	6	.98	64	.002	<1	.43	.048	.14	1	1	6.0	<1	4.98	1
0384	1.0	127	5	92	.1	70	45	1056	8.23	23	1	<2	1	42	<.2	.8	<.5	23	1.18	.210	6	8	.78	59	.002	<1	.47	.054	.17	1	1	4.6	2	4.34	2
0385	1.4	119	7	81	.2	55	42	799	10.53	51	1	<2	1	50	<.2	<.5	<.5	17	1.44	.183	5	7	.74	51	.001	<1	.39	.038	.16	2	2	4.0	<1	7.39	1
0386	1.5	154	7	75	.2	81	60	936	11.76	89	1	<2	1	58	<.2	1.0	<.5	20	1.74	.165	5	8	.77	56	.002	<1	.44	.030	.18	2	2	4.1	3	8.41	1
0387	2.1	170	11	183	.1	68	61	1194	11.49	63	1	<2	1	44	.2	2.1	<.5	27	1.11	.201	6	8	.63	41	.001	<1	.43	.056	.13	2	1	5.7	2	7.43	1
0388	1.2	163	5	138	.1	66	63	979	8.29	36	1	<2	1	61	.2	1.1	<.5	28	1.61	.203	6	9	.73	38	.001	2	.52	.065	.17	2	1	5.7	2	4.86	2
0389	1.6	185	7	122	.1	61	59	928	9.75	36	1	<2	1	50	<.2	1.6	<.5	28	1.21	.206	6	9	.62	48	.002	2	.54	.062	.16	2	2	4.8	3	6.36	1
0390	3.4	148	7	231	.1	64	51	1775	15.39	48	1	<2	1	44	.4	<.5	<.5	24	1.12	.173	5	8	.81	48	.002	6	.36	.047	.12	2	2	5.6	3	9.77	1
STANDARD C3	27.1	70	38	170	5.3	36	12	808	3.36	57	26	2	21	29	21.8	16.2	23.0	81	.60	.093	22	177	.62	157	.086	23	1.85	.040	.17	16	1	4.7	<1	.03	6
STANDARD G-2	1.4	4	2	44	<.1	7	4	537	2.01	<1	3	<2	5	69	<.2	<.5	<.5	41	.65	.101	10	78	.60	228	.124	2	.91	.074	.46	2	<1	2.6	<1	<.01	4

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 6 2000 DATE REPORT MAILED: Oct 14/00 SIGNED BY: C. Toye

D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD 2000 File # A001978R

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0319	3.8	26	16	56	<.1	35	12	145	4.73	68	1	<2	4	14	.4	2.9	.6	3	.30	.029	7	17	.24	64	.001	3	.31	.017	.19	1	7	.9	<1	4.24	1
0320	.7	36	17	63	<.1	36	13	208	4.43	28	2	<2	5	13	.3	1.3	<.5	3	.30	.033	8	11	.37	73	.001	3	.33	.019	.19	3	2	1.0	<1	3.32	1
0321	2.6	104	22	142	.3	69	34	283	13.11	94	1	<2	1	59	.8	7.1	<.5	15	1.36	.238	2	9	.52	35	.002	5	.48	.019	.25	2	20	2.9	2	12.13	2
0322	2.6	88	4	51	.2	132	35	925	5.34	10	2	<2	1	184	.2	<.5	.8	13	5.50	.190	3	27	2.03	169	.001	2	.43	.019	.23	1	<1	4.0	<1	1.80	2
0323	.9	122	3	39	<.1	120	40	601	4.59	21	1	<2	2	50	.3	<.5	<.5	11	1.21	.089	4	18	.90	116	.001	3	.42	.017	.22	2	<1	3.7	<1	1.77	1
0324	3.1	139	7	85	.2	109	40	555	8.67	51	1	<2	2	50	.4	3.1	2.0	19	1.03	.227	2	14	.89	42	.002	3	.51	.019	.27	1	5	4.8	<1	5.82	2
0325	1.8	129	14	133	.3	83	53	169	9.48	78	<1	<2	2	47	.7	3.7	.7	19	.85	.272	2	9	.34	32	.002	4	.51	.017	.27	2	6	3.1	2	8.88	2
0326	2.6	127	7	145	.1	57	43	69	4.87	27	1	<2	1	37	.3	.6	<.5	18	.61	.251	4	10	.13	39	.002	2	.51	.019	.27	1	2	2.5	<1	4.70	1
0327	1.5	164	8	165	.2	72	44	172	7.58	32	<1	<2	1	42	.3	.8	<.5	19	.69	.262	3	9	.28	32	.002	8	.49	.018	.26	2	3	2.9	1	6.85	2
0328	4.0	145	7	138	.1	64	38	226	6.29	28	1	<2	1	50	.3	1.5	1.0	18	.96	.222	3	12	.38	39	.002	2	.49	.019	.26	1	4	3.4	<1	5.62	2
0330	3.4	133	8	190	.1	85	45	88	6.54	34	<1	<2	2	38	.6	2.1	<.5	18	.71	.266	4	11	.26	34	.002	1	.53	.020	.27	1	5	2.9	2	5.87	2
0331	1.3	166	6	124	.2	68	47	505	6.82	22	<1	<2	2	40	.4	.7	<.5	18	.78	.229	5	8	.33	32	.001	2	.52	.028	.24	2	4	3.8	1	5.59	2
0332	4.0	147	8	152	.2	72	55	321	9.19	37	<1	<2	1	44	.6	1.5	<.5	19	.97	.253	4	10	.24	28	.002	3	.50	.038	.21	1	3	3.0	1	8.37	1
RE 0332	4.0	145	8	149	.2	73	55	322	9.12	37	<1	<2	2	44	.6	.9	<.5	17	.96	.255	4	10	.24	29	.002	2	.50	.038	.21	<1	3	2.9	1	8.39	1
0334	1.2	236	6	64	.2	77	60	940	7.66	13	<1	<2	2	38	.2	1.0	<.5	26	.77	.216	6	7	.51	34	.002	2	.46	.065	.18	1	3	4.7	<1	4.47	2
0335	2.0	192	5	77	.1	77	50	1366	7.97	5	<1	<2	2	41	<.2	1.2	<.5	26	.79	.233	7	8	.74	69	.001	<1	.46	.083	.16	<1	2	6.5	1	3.06	3
0336	1.3	164	8	169	.2	106	58	919	7.66	19	<1	<2	2	44	.7	.8	<.5	24	.95	.204	4	7	.69	42	.001	2	.53	.070	.20	1	5	5.6	<1	4.22	2
0337	2.0	136	7	98	.1	119	62	836	6.63	20	<1	<2	2	49	.4	.7	<.5	21	1.07	.201	4	9	.65	53	.001	1	.57	.063	.21	<1	3	5.1	<1	3.57	2
0338	1.1	144	8	114	.1	168	60	1286	10.48	53	<1	<2	1	67	.4	2.6	<.5	18	1.66	.120	2	15	1.12	29	.001	2	.49	.058	.20	1	4	6.7	<1	6.00	1
0339	1.6	127	3	105	.2	146	50	1528	8.09	9	<1	<2	1	66	.2	<.5	<.5	17	1.48	.125	3	14	1.33	120	.001	6	.47	.043	.22	<1	1	7.3	1	2.20	1
0340	1.8	26	14	59	<.1	37	12	141	5.58	62	1	<2	4	19	.4	4.2	.6	5	.40	.050	6	10	.17	45	.001	4	.32	.016	.19	3	3	1.0	<1	5.48	1
0341	13.9	13	16	19	.4	109	30	194	9.68	626	2	<2	3	31	<.2	2.2	8.1	15	.53	.087	4	20	.14	38	.001	3	.35	.011	.19	1	<1	1.4	<1	9.77	1
STANDARD C3	26.4	69	36	168	5.3	37	14	839	3.32	58	24	<2	21	29	25.5	14.7	23.3	81	.60	.096	18	180	.62	160	.090	21	1.82	.043	.17	16	1	4.4	<1	.03	8
STANDARD G-2	1.5	3	2	42	<.1	7	4	543	1.98	<1	2	<2	5	68	<.2	<.5	<.5	40	.64	.099	7	75	.59	222	.127	<1	.89	.077	.49	2	<1	2.4	<1	<.01	5

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 6 2000 DATE REPORT MAILED: Oct 16/00 SIGNED BY. ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ____

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD File # A001626R

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: R. Hall

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0124	1.2	43	2	94	.1	49	22	1574	5.17	27	1	<2	4	27	<.2	.5	<.5	8	.79	.056	16	11	1.04	111	<.001	5	.38	.019	.21	1	<1	2.8	<1	.42	1
0127	.6	75	22	40	.3	79	31	1609	4.87	39	1	<2	1	277	<.2	<.5	.5	19	8.48	.117	2	16	3.31	90	.001	10	.38	.017	.22	1	<1	7.5	<1	.73	1
0132	2.2	51	417	93	1.9	34	19	1222	3.91	35	1	<2	1	206	.5	1.5	21.6	14	6.59	.149	4	11	2.43	122	.001	6	.47	.017	.23	1	<1	5.6	<1	.79	1
0135	3.1	64	38	51	.6	75	34	1322	6.48	61	1	<2	1	213	<.2	1.1	4.1	15	7.32	.102	3	13	2.43	160	.001	6	.35	.013	.21	<1	<1	5.4	<1	2.35	1
0138	1.9	70	151	50	3.4	88	32	851	5.47	39	1	<2	3	169	<.2	.9	9.5	10	6.24	.081	3	16	1.84	142	.001	8	.37	.014	.20	2	<1	4.6	<1	1.49	1
0141	3.1	40	8	63	<.1	50	26	869	4.85	10	2	<2	3	84	<.2	<.5	<.5	7	1.89	.084	10	14	1.20	123	.001	4	.39	.015	.24	1	<1	1.6	<1	1.29	1
0144	.6	48	4	55	<.1	34	15	278	3.32	3	2	<2	7	13	<.2	<.5	<.5	3	.24	.038	16	13	.76	73	<.001	2	.36	.013	.21	4	<1	.5	<1	.70	<1
0147	.6	28	5	29	<.1	28	11	387	3.05	3	2	<2	7	32	<.2	.8	<.5	4	.67	.029	16	14	.80	96	<.001	6	.33	.009	.20	5	<1	1.9	<1	.79	<1
0150	3.6	29	4	40	<.1	31	11	465	3.06	5	2	<2	9	19	<.2	.5	<.5	4	.35	.035	20	17	.83	94	<.001	5	.37	.012	.20	2	<1	1.1	<1	.33	1
0154	2.9	38	7	57	<.1	37	12	363	3.05	1	3	<2	6	50	<.2	.9	<.5	4	1.23	.043	14	17	.84	116	<.001	2	.41	.016	.18	1	<1	.9	<1	.74	1
0157	2.3	114	10	221	.1	56	40	280	5.06	30	1	<2	1	85	.7	.5	<.5	20	1.98	.270	8	11	.50	60	.002	7	.54	.019	.25	3	1	3.0	<1	4.44	1
0160	7.6	103	12	162	.4	70	41	295	8.99	36	1	<2	1	38	.9	5.8	<.5	24	.89	.231	6	15	.47	37	.002	4	.51	.014	.21	2	6	1.7	<1	7.59	1
0163	9.7	98	6	287	.2	55	35	93	4.64	20	1	<2	1	50	.9	1.8	<.5	30	1.13	.353	7	14	.18	60	.002	4	.59	.019	.25	4	2	1.7	<1	4.24	1
0167	3.8	171	10	54	.2	79	50	512	11.26	81	1	<2	2	70	<.2	1.5	<.5	19	1.56	.186	6	13	.63	33	.001	2	.68	.020	.14	1	4	3.4	<1	9.73	1
0171	3.4	106	7	91	.2	84	47	938	9.04	127	1	<2	1	70	.2	2.7	<.5	17	1.36	.289	7	13	.85	53	.001	2	.67	.032	.21	<1	8	4.4	2	5.95	1
0176	2.0	89	11	157	.4	45	37	873	8.59	120	1	<2	2	78	.9	1.1	.8	21	1.33	.258	6	6	.84	31	.001	2	.99	.031	.16	2	4	3.7	<1	5.86	2
0180	1.5	187	3	96	.1	85	57	1127	7.56	18	1	<2	1	94	<.2	<.5	<.5	37	2.05	.153	7	9	1.30	115	.001	5	.45	.039	.17	1	<1	8.5	<1	1.80	2
0184	3.7	125	7	100	.1	63	52	915	10.20	44	1	<2	1	74	.2	.9	<.5	22	1.49	.165	5	14	.72	39	.001	7	.49	.036	.20	1	1	5.2	<1	7.51	1
0188	2.0	131	<2	86	<.1	63	48	1242	7.13	4	1	<2	1	67	<.2	<.5	<.5	27	1.31	.172	6	9	1.09	170	.001	2	.48	.034	.19	<1	<1	4.7	<1	1.54	2
RE 0188	1.8	129	2	84	.1	62	47	1228	7.08	5	1	<2	1	67	<.2	<.5	<.5	28	1.30	.170	6	8	1.09	169	.001	2	.47	.033	.19	<1	<1	4.5	<1	1.52	2
0192	2.7	104	3	77	.1	50	40	1116	7.29	7	1	<2	1	44	<.2	.5	<.5	21	.75	.196	8	10	.67	51	.001	2	.47	.033	.17	1	<1	3.7	<1	3.20	1
0196	.8	107	6	108	.1	55	37	848	8.14	26	1	<2	1	74	<.2	1.1	<.5	33	1.51	.132	5	10	.91	64	.002	5	.60	.015	.18	2	8	3.4	2	4.91	2
0200	.7	212	3	47	.2	41	22	391	2.94	4	1	<2	1	95	<.2	<.5	<.5	13	1.68	.145	8	13	.58	155	.001	8	.36	.016	.16	3	<1	2.3	<1	1.25	1
0204	.3	45	3	71	<.1	34	12	758	4.04	3	2	<2	6	73	<.2	1.7	<.5	4	2.32	.030	7	14	1.13	72	<.001	4	.22	.007	.14	5	<1	1.4	<1	1.43	<1
0208	2.7	130	4	72	.2	51	33	713	5.21	37	1	<2	1	99	<.2	3.2	<.5	19	2.40	.196	7	12	1.13	124	.001	5	.42	.012	.22	1	<1	4.0	<1	1.91	1
STANDARD C3	25.4	67	38	168	5.6	38	12	820	3.40	61	25	3	23	31	23.5	15.5	24.3	85	.64	.093	23	188	.66	171	.090	25	1.88	.042	.17	15	1	4.0	<1	.03	7
STANDARD G-2	1.3	3	3	42	<.1	7	4	562	2.05	<1	3	<2	5	74	<.2	<.5	<.5	42	.71	.097	11	81	.66	239	.133	2	.94	.078	.50	2	<1	1.8	<1	<.01	4

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 6 2000 DATE REPORT MAILED: Oct 16/00 SIGNED BY. C. Leong D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data___ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD File # A001602R

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0215	2.4	60	3	144	.2	60	23	1159	4.33	8	2	<2	<1	214	.6	1.3	<.5	17	5.80	.110	2	13	2.13	150	.011	5	.46	.021	.23	2	<1	5.3	<1	1.63	1
0218	7.4	174	4	213	.2	120	20	442	5.56	33	1	<2	1	92	1.1	.7	<.5	37	1.91	.336	3	32	.52	111	.002	4	.43	.015	.20	6	<1	2.5	<1	4.38	1
RE 0218	7.2	164	4	202	.2	118	20	422	5.14	31	2	<2	1	88	1.2	.7	<.5	34	1.81	.332	4	29	.49	123	.002	9	.40	.014	.19	5	<1	2.3	<1	4.17	2

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 6 2000 DATE REPORT MAILED: Oct 16/00 SIGNED BY: C. Leong D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A001846R
305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0015	1.2	41	16	56	.4	53	30	1295	4.94	140	1	<2	<1	203	.6	1.5	.9	17	7.53	.142	2	8	2.65	166	.002	6	.38	.017	.20	1	<1	6.8	<1	1.59	2
0018	4.1	84	13	57	.4	98	33	923	5.85	38	1	<2	<1	198	.2	3.5	<.5	11	8.26	.099	2	10	2.48	118	.001	4	.27	.030	.15	1	<1	7.6	<1	1.51	1
0020	.6	25	4	71	.1	34	13	515	3.31	2	1	<2	4	53	<.2	<.5	<.5	5	1.09	.036	8	9	.88	81	<.001	2	.29	.016	.13	1	<1	2.1	<1	.59	1
0023	1.4	31	5	96	.1	33	13	418	3.72	2	1	<2	4	63	<.2	<.5	<.5	6	1.33	.043	8	11	1.07	82	<.001	4	.36	.017	.17	1	<1	2.1	<1	.78	2
0026	1.4	32	6	42	.1	35	13	496	3.38	55	1	<2	4	50	.2	1.7	<.5	5	1.20	.034	7	8	.85	77	<.001	2	.27	.010	.16	2	<1	3.2	<1	1.35	1
0029	1.2	31	5	40	<.1	27	13	271	2.90	9	1	<2	6	15	<.2	.9	<.5	3	.28	.032	10	9	.54	77	.001	3	.34	.016	.20	2	<1	1.1	<1	1.23	2
0032	.8	34	5	36	<.1	32	12	337	2.79	4	1	<2	3	30	<.2	<.5	<.5	4	.73	.033	8	10	.61	103	<.001	3	.32	.018	.19	3	<1	1.3	<1	1.13	1
0035	3.5	124	6	113	.3	160	44	696	7.89	9	2	<2	5	128	.4	<.5	.5	16	3.28	.156	2	25	1.54	84	.002	1	.43	.019	.24	1	<1	5.0	<1	3.92	2
0039	3.7	126	4	192	.2	53	37	645	6.70	1	<1	<2	<1	48	.5	<.5	<.5	22	.82	.335	6	10	.75	82	.002	8	.57	.030	.30	1	<1	3.5	<1	2.62	3
0041	3.6	112	6	150	.1	98	46	388	5.86	13	1	<2	<1	39	.2	.7	<.5	17	.65	.167	3	20	.56	54	.001	1	.48	.023	.24	1	1	3.7	1	3.66	2
0044	2.4	122	4	161	.1	61	46	1167	6.75	5	<1	<2	<1	40	.4	<.5	<.5	23	.69	.286	8	11	.65	66	.002	2	.46	.065	.20	<1	1	5.1	<1	2.32	3
0049	1.1	137	5	109	.3	155	56	1326	9.85	25	<1	<2	<1	148	<.2	1.3	<.5	26	3.79	.114	2	29	1.89	90	.001	<1	.62	.038	.17	<1	1	7.2	1	3.48	3
0051	.8	107	2	89	.2	77	44	1134	6.61	3	<1	<2	<1	97	<.2	<.5	<.5	33	2.49	.141	3	36	1.46	192	.001	3	.88	.053	.17	1	<1	7.7	<1	1.43	4
0055	4.6	122	3	98	.1	67	41	1625	9.67	14	<1	<2	<1	66	<.2	<.5	<.5	27	1.47	.135	3	11	1.42	94	.002	<1	.59	.072	.16	<1	<1	6.3	1	2.84	3
0057	2.9	103	6	93	.1	49	48	791	7.72	23	<1	<2	<1	73	<.2	.9	<.5	26	1.28	.262	5	12	.84	37	.001	3	.60	.043	.22	<1	1	6.6	1	4.14	3
0060	1.1	71	5	75	.1	51	42	891	6.76	34	<1	<2	<1	56	<.2	1.2	<.5	22	1.16	.284	6	9	.63	51	.002	<1	.55	.051	.24	1	1	4.0	1	3.61	3
0063	2.0	100	2	69	.1	41	32	1566	6.68	8	<1	<2	<1	55	<.2	<.5	<.5	22	1.00	.280	6	11	1.04	324	.002	1	.57	.037	.24	<1	<1	6.6	2	.90	3
RE 0063	1.9	98	2	67	.1	38	30	1523	6.55	8	<1	<2	<1	55	<.2	<.5	<.5	20	.97	.271	6	10	1.02	318	.002	2	.55	.035	.23	<1	<1	6.5	<1	.87	3
0067	4.5	71	3	77	.2	30	28	1911	8.40	8	<1	<2	1	171	<.2	<.5	<.5	26	4.04	.171	3	12	1.82	175	.002	1	.47	.026	.22	<1	<1	5.9	<1	1.49	2
0071	2.6	161	6	58	.2	64	56	1141	7.90	18	<1	<2	<1	79	<.2	<.5	<.5	30	1.81	.206	4	12	1.01	55	.002	3	.45	.047	.20	<1	<1	6.1	<1	3.93	3
0074	3.2	225	5	77	.2	88	71	1447	10.68	34	<1	<2	<1	68	<.2	1.2	<.5	43	1.54	.205	5	16	1.31	76	.003	<1	.85	.047	.18	<1	1	6.4	1	4.40	4
0077	1.1	130	4	96	.3	60	42	1098	7.81	17	<1	<2	1	193	.2	<.5	<.5	35	3.74	.183	2	14	2.02	144	.002	<1	.70	.035	.20	1	<1	6.2	<1	2.53	4
0083	.6	140	3	134	.2	70	56	1354	8.71	9	<1	<2	<1	72	<.2	<.5	<.5	32	1.56	.167	3	11	1.38	114	.003	<1	.99	.040	.20	1	1	6.6	<1	2.23	5
0086	.8	57	2	129	.2	36	35	1820	8.06	<1	<1	<2	<1	128	<.2	<.5	<.5	38	3.56	.200	6	5	1.70	140	.010	<1	.58	.041	.18	<1	<1	5.8	<1	.71	4
STANDARD C3	26.8	67	37	173	5.6	39	13	862	3.49	59	24	<2	21	29	22.6	15.4	23.7	84	.62	.100	19	185	.64	166	.092	23	1.88	.042	.18	15	1	4.6	<1	.03	10
STANDARD G-2	1.4	2	2	43	<.1	7	4	547	1.99	<1	2	<2	4	70	<.2	<.5	<.5	39	.64	.098	7	75	.60	220	.129	<1	.91	.079	.49	2	<1	2.4	<1	<.01	5

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 6 2000 DATE REPORT MAILED: Oct 14/00 SIGNED BY. C. Leong ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD File # A001361R

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 172001	1.2	50	3	139	<.1	84	25	1412	4.60	41	1	<2	4	71	.2	<.5	<.5	11	2.38	.077	14	20	1.60	124	<.001	3	.45	.027	.22	<1	<1	4.4	<1	.71	1
B 172002	1.3	48	3	106	.1	41	15	1115	3.89	12	1	<2	3	118	.3	<.5	<.5	11	3.40	.079	10	5	1.68	79	<.001	2	.34	.023	.12	<1	<1	5.0	<1	.79	<1
B 172003	1.6	27	2	30	<.1	17	5	545	1.72	10	1	<2	4	88	.2	<.5	<.5	6	2.63	.050	15	7	1.22	107	<.001	2	.24	.012	.12	<1	<1	2.5	<1	.46	1
B 172004	.9	79	5	77	<.1	151	39	1513	6.02	11	1	<2	<1	296	.2	.5	<.5	33	7.81	.082	3	66	3.94	143	.001	2	.45	.015	.10	1	<1	10.1	<1	1.23	1
B 172005	1.0	80	4	77	.1	185	49	1738	7.08	9	1	<2	<1	352	<.2	<.5	<.5	88	8.54	.114	3	184	4.76	111	.002	3	1.01	.020	.05	<1	<1	17.1	2	1.67	4
B 172006	1.0	77	5	93	.1	152	48	1783	8.80	8	<1	<2	<1	276	<.2	<.5	.6	92	7.27	.111	2	126	4.76	167	.001	<1	1.17	.018	.06	<1	<1	16.3	<1	1.85	3
B 172007	4.7	80	6	64	<.1	186	37	1107	5.08	26	1	<2	<1	246	<.2	<.5	<.5	18	11.14	.082	3	23	3.29	145	<.001	2	.29	.025	.09	<1	<1	9.9	<1	2.14	<1
B 172008	1.0	85	6	59	<.1	229	41	1068	4.97	116	1	<2	1	302	<.2	<.5	.5	16	12.93	.083	3	28	3.75	132	.001	4	.28	.031	.10	<1	<1	9.3	<1	2.29	1
B 172009	1.6	90	9	59	.1	219	45	1075	5.81	35	<1	<2	1	309	<.2	<.5	<.5	14	12.54	.071	2	22	3.73	121	.001	2	.28	.020	.10	<1	<1	9.4	<1	2.88	<1
B 172010	3.9	134	14	108	.2	114	50	1376	9.17	13	1	<2	1	223	<.2	3.8	.5	19	6.09	.151	2	10	2.53	64	<.001	<1	.31	.012	.11	1	1	6.4	<1	4.88	<1
B 172011	1.8	28	15	58	.1	30	13	287	4.95	57	2	<2	4	23	<.2	2.1	<.5	4	.68	.028	9	9	.48	61	<.001	1	.28	.011	.14	1	6	1.6	1	4.60	<1
B 172012	1.9	124	13	235	.2	79	45	100	8.01	29	1	<2	1	36	.3	2.2	.5	21	.79	.282	6	9	.22	23	.001	3	.50	.018	.21	2	8	2.8	3	7.36	<1
B 172013	.9	24	2	68	<.1	34	12	351	2.53	2	2	<2	5	11	<.2	<.5	<.5	5	.19	.043	11	9	.57	121	.001	<1	.54	.011	.13	1	<1	1.0	<1	1.09	1
B 172014	.3	38	2	78	.1	46	18	248	2.64	3	2	<2	4	15	<.2	<.5	<.5	6	.22	.075	10	11	.41	158	.001	<1	.45	.013	.15	2	<1	1.3	<1	1.35	<1
B 172015	7.3	105	8	296	.1	125	48	397	7.01	45	6	<2	1	71	1.3	2.3	<.5	24	1.54	.265	6	17	.70	30	.001	2	.45	.012	.18	1	6	3.4	2	6.63	<1
B 172016	3.3	94	6	222	.1	79	34	255	4.87	17	4	<2	1	73	.8	1.1	<.5	27	1.45	.349	7	9	.51	32	.002	3	.55	.015	.23	2	1	3.3	<1	4.55	1
RE B 172016	3.6	94	6	223	.1	81	34	266	5.07	17	4	<2	1	76	.8	1.2	<.5	28	1.50	.350	7	10	.53	31	.002	<1	.57	.015	.24	2	<1	3.5	1	4.56	<1
B 172017	3.6	84	5	181	.1	115	40	229	5.04	22	3	<2	1	38	.8	1.2	<.5	21	.78	.276	6	12	.49	32	.001	3	.45	.010	.17	1	1	2.8	<1	4.44	<1
B 172018	4.3	91	9	229	.2	132	48	300	5.90	37	4	<2	1	50	1.1	1.2	<.5	20	1.06	.164	6	18	.46	26	.001	3	.40	.011	.18	2	2	3.3	1	5.81	<1
B 172019	4.4	88	8	168	.2	140	24	234	5.37	98	2	<2	4	52	.4	16.5	<.5	15	.73	.179	8	21	.39	43	<.001	<1	.38	.010	.17	2	<1	2.9	<1	4.12	<1
B 172020	.5	19	4	50	.6	16	6	465	1.93	2224	1	<2	5	140	.4	6.0	<.5	3	2.23	.022	9	8	.96	65	<.001	3	.22	.007	.13	3	<1	2.5	<1	1.18	<1
B 172021	1.3	19	5	53	.1	22	10	624	2.52	364	2	<2	6	127	<.2	.5	<.5	4	2.97	.028	11	7	1.36	65	<.001	2	.24	.008	.15	1	<1	2.5	<1	.81	<1
B 172022	.2	33	7	50	.5	20	8	720	2.68	517	1	<2	4	153	<.2	4.4	<.5	4	2.49	.026	8	6	1.15	45	<.001	1	.18	.005	.11	2	<1	3.2	<1	1.43	<1
B 172023	1.5	55	13	145	1.2	38	18	684	3.49	544	2	<2	4	101	<.2	11.7	<.5	3	1.66	.032	10	9	.93	69	<.001	<1	.32	.009	.19	1	<1	2.6	<1	2.15	<1
B 172024	.2	191	248	95	14.1	44	17	475	2.97	392	2	<2	4	100	.3	83.5	.9	2	1.44	.035	8	7	.73	55	<.001	<1	.25	.005	.15	2	<1	2.2	<1	2.60	<1
STANDARD C3	27.8	68	35	177	5.4	37	12	841	3.09	57	26	2	22	30	23.1	15.7	23.4	82	.62	.097	22	181	.64	165	.086	20	1.86	.040	.16	15	2	4.7	<1	.03	6
STANDARD G-2	1.8	3	2	45	<.1	7	4	559	1.82	<1	3	<2	4	73	<.2	<.5	<.5	42	.70	.105	10	79	.63	238	.130	<1	.94	.079	.48	2	<1	2.6	<1	<.01	4

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 6 2000 DATE REPORT MAILED: Oct 14/00 SIGNED BY..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ____

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

WHOLE ROCK ICP ANALYSIS

Standard Drilling PROJECT CARIBOO GOLD File # A001465R2

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	SiO2 %	Al2O3 %	Fe2O3 %	MgO %	CaO %	Na2O %	K2O %	TiO2 %	P2O5 %	MnO %	Cr2O3 %	Ba ppm	Ni ppm	Sr ppm	Zr ppm	Y ppm	Nb ppm	Sc ppm	LOI %	TOT/C %	TOT/S %	SUM %
B 169980	22.86	11.86	12.35	7.20	15.49	.74	2.92	2.75	.54	.24	.025	2229	46	470	154	27	36	26	22.6	6.14	4.05	99.92
B 169983	30.91	10.06	9.48	6.88	14.90	1.50	2.12	.91	.18	.17	.043	2023	119	289	52	12	16	23	22.5	6.32	2.42	99.94
B 169986	35.24	13.48	10.17	4.16	11.29	2.48	2.72	2.64	.52	.13	.026	2521	89	350	155	20	32	25	16.7	4.61	2.58	99.92
B 169990	38.96	28.81	8.13	2.70	.97	.67	7.27	1.19	.12	.09	.022	2568	28	184	232	48	26	25	10.5	1.98	.73	99.79
B 169991	34.35	24.69	6.37	2.90	5.81	.58	6.53	4.90	.61	.16	.016	3691	40	316	324	45	65	50	12.3	2.57	1.16	99.74
B 169993	47.73	16.66	11.73	2.38	1.50	1.89	3.40	3.02	.35	.23	.018	2406	52	134	177	25	38	30	10.7	2.68	.16	99.94
B 169995	41.29	17.59	14.51	2.62	2.68	2.40	3.36	3.06	.30	.16	.023	2146	73	175	178	23	39	31	11.6	2.68	3.82	99.90
B 169997	39.84	14.24	17.07	3.26	4.59	1.47	1.97	2.68	.33	.16	.012	2195	<20	193	166	22	36	26	14.0	3.24	5.24	99.93
B 170000	44.20	13.33	15.73	2.56	3.60	1.32	1.90	3.40	.51	.19	.008	1570	52	153	218	29	50	28	12.9	2.89	4.34	99.89
B 172030	47.90	15.28	11.31	3.01	3.86	2.20	2.30	2.41	.27	.14	.025	2170	56	183	138	17	30	28	10.9	2.73	1.91	99.90
B 172033	55.58	13.71	9.45	1.60	2.46	.42	4.04	3.29	.53	.05	.010	3241	51	120	206	25	40	25	8.2	1.39	4.57	99.76
RE B 172033	55.78	13.77	9.63	1.61	2.48	.41	3.70	3.31	.52	.05	.007	3255	61	120	205	24	46	25	8.2	1.37	4.58	99.89
STANDARD SO-15/CSB	49.81	12.33	7.25	7.21	5.83	2.39	1.84	1.78	2.68	1.38	1.052	2046	80	393	982	22	30	13	5.9	2.48	5.51	99.88

GROUP 4A - 0.200 GM SAMPLE BY LIBO2 FUSION, ANALYSIS BY ICP-ES. LOI BY LOSS ON IGNITION.
TOTAL C & S BY LECO. (NOT INCLUDED IN THE SUM)
- SAMPLE TYPE: CORE PULP
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 6 2000 DATE REPORT MAILED: Oct 18/00 SIGNED BY ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ____

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A001465R2

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	Al %	Na %	K %	W ppm	Zr ppm	Ce ppm	Sn ppm	Y ppm	Nb ppm	Ta ppm	Be ppm	Sc ppm	Li ppm	S %	Rb ppm	Hf ppm
B 169983	5.6	55	7	55	<.2	127	37	1225	6.68	24	<1	<4	3	265	.4	1	3	143	9.33	.066	10	194	3.85	454	.085	5.21	1.155	1.47	3	37.2	22	<.5	5.5	2.0	<.5	1	23	14	2.33	56	<1
B 169984	3.7	61	7	55	<.2	141	39	1095	6.62	41	<1	<4	<1	332	.5	2	4	165	8.87	.064	7	261	3.56	676	.085	6.13	1.753	1.54	210	29.8	15	<.5	5.0	.7	<.5	1	27	23	1.74	68	1
B 169985	2.5	34	7	52	<.2	124	40	1164	6.07	37	<1	<4	1	389	.4	2	3	188	9.18	.105	9	215	3.47	1518	.111	6.91	1.974	1.77	4	30.1	20	.6	7.1	2.7	<.5	1	30	9	1.10	85	<1
B 169986	3.7	57	9	93	.2	108	34	991	7.04	31	<1	<4	<1	327	.5	3	5	205	7.81	.207	19	130	2.42	449	.237	7.03	1.876	1.83	11	41.3	39	<.5	8.8	5.4	<.5	1	24	12	2.38	88	1
B 169987	3.8	74	9	69	.3	46	31	1142	8.35	12	<1	<4	<1	299	.4	3	4	206	7.01	.200	19	43	1.96	227	.317	6.72	2.432	1.61	7	53.1	42	.8	8.3	7.7	<.5	1	23	7	3.66	75	1
B 169988	4.8	135	15	65	.4	65	43	1365	9.79	19	<1	<4	<1	348	.4	1	5	234	6.29	.165	19	41	2.24	542	.353	7.19	2.919	1.51	7	63.8	41	1.0	8.2	5.0	<.5	1	27	7	5.09	92	1
B 169989	1.8	131	7	41	.4	51	24	1581	6.48	37	4	<4	11	454	<.2	4	3	175	5.49	.063	31	85	2.53	1854	.241	11.27	.507	4.40	5	108.0	62	3.0	9.6	4.6	<.5	3	24	12	1.95	303	3
B 169990	1.2	12	7	50	<.2	52	21	790	5.94	22	8	<4	20	170	<.2	5	2	176	.69	.054	48	115	1.55	2379	.215	14.07	.500	6.36	3	122.7	88	6.3	6.9	4.4	1.1	5	25	13	.88	366	4
B 169991	1.1	<1	3	26	<.2	52	44	1203	4.36	11	<1	<4	2	282	.3	7	5	440	4.27	.243	10	54	1.63	1884	.498	12.07	.438	5.33	12	40.4	22	4.0	10.6	12.6	.7	5	47	13	1.28	339	1
B 169992	.7	95	<3	81	<.2	100	62	2320	10.54	27	1	<4	<1	168	1.0	1	1	339	2.76	.161	15	72	2.38	1981	.343	9.72	.581	3.50	7	50.0	31	1.2	7.2	5.7	<.5	3	39	9	.24	254	1
B 169993	1.0	118	<3	95	<.2	69	37	1782	8.37	17	1	<4	3	127	.4	<1	2	256	1.03	.148	24	73	1.37	2302	.350	8.76	1.464	2.46	4	66.2	44	<.5	6.1	6.6	.6	2	30	14	.16	138	2
B 169994	.7	56	3	86	<.2	85	47	1936	10.00	18	1	<4	3	196	.4	1	2	287	2.11	.140	10	102	1.83	1851	.290	9.65	1.864	2.49	3	75.5	24	.7	5.9	5.5	.8	2	33	19	.91	156	2
B 169995	1.2	128	5	74	.3	76	54	1235	9.97	10	2	<4	1	151	.5	1	3	250	2.07	.129	13	77	1.43	840	.250	8.79	1.856	2.18	4	59.9	28	<.5	5.4	2.5	<.5	2	28	18	3.18	138	1
B 169996	.9	100	5	78	<.2	94	44	1256	8.76	17	<1	<4	1	169	.4	2	<1	236	3.33	.108	10	123	1.72	798	.233	7.90	1.006	2.00	3	34.4	21	<.5	4.4	4.4	<.5	2	29	22	2.41	109	<1
B 169997	1.6	92	5	115	<.2	57	35	1271	12.54	4	<1	<4	1	164	.5	3	1	218	3.51	.130	15	44	1.87	646	.262	7.42	1.113	1.37	5	31.4	34	<.5	5.6	<.2	<.5	1	26	35	4.59	64	<1
B 169998	1.0	67	3	92	<.2	58	36	1381	7.86	<2	<1	<4	2	186	.4	2	2	245	4.07	.147	17	63	1.90	1862	.352	6.90	2.123	1.31	2	27.5	32	<.5	5.4	8.9	<.5	1	25	25	.51	60	1
B 169999	2.2	135	4	63	<.2	56	40	1232	7.17	3	<1	<4	2	171	.4	3	1	284	3.86	.177	18	35	1.37	356	.453	7.34	2.620	1.50	3	29.9	34	<.5	5.4	11.1	<.5	1	27	12	2.09	67	1
B 170000	3.9	174	6	96	<.2	48	48	1430	11.73	<2	1	<4	2	131	.5	2	<1	257	2.72	.167	17	29	1.41	164	.249	7.04	1.079	1.26	4	24.5	33	<.5	5.3	1.6	<.5	1	26	16	4.21	51	1
RE B 170000	3.8	172	6	96	<.2	48	48	1434	11.66	3	2	<4	2	131	.5	2	1	261	2.72	.170	19	29	1.42	189	.271	7.07	1.078	1.26	4	27.4	36	<.5	5.5	2.0	<.5	1	27	16	4.20	53	<1
RRE B 170000	3.8	169	6	95	<.2	48	47	1423	11.79	2	1	<4	1	129	.6	1	2	263	2.71	.167	16	28	1.41	208	.288	7.00	1.060	1.25	4	26.2	35	<.5	5.3	1.6	<.5	1	26	15	4.13	51	1
B 172028	1.4	124	5	81	<.2	42	36	1238	9.54	<2	2	<4	1	167	.5	2	3	267	2.68	.173	20	37	1.35	594	.343	7.82	2.484	1.30	2	72.3	39	<.5	6.8	5.7	<.5	1	27	20	2.93	60	1
B 172029	1.8	84	4	83	<.2	43	30	1213	8.54	<2	<1	<4	<1	167	.4	1	1	210	3.00	.122	13	35	1.55	255	.215	7.11	2.036	1.27	3	24.5	27	<.5	4.4	3.1	<.5	1	23	19	2.65	55	<1
B 172030	1.1	102	4	97	<.2	79	39	1148	8.13	<2	<1	<4	<1	162	.3	1	2	210	2.93	.108	9	138	1.74	545	.187	7.95	1.720	1.66	2	20.2	20	<.5	3.5	2.2	<.5	1	28	25	1.74	80	1
B 172031	.9	78	3	85	<.2	89	32	1059	6.54	2	<1	<4	2	201	.5	2	2	216	3.84	.104	8	176	1.89	2179	.199	8.19	1.766	1.86	2	18.9	16	<.5	3.7	2.6	<.5	1	29	28	.73	93	<1
B 172032	1.1	204	5	72	<.2	64	52	1093	7.96	2	2	<4	2	103	.3	<1	1	263	1.33	.179	22	35	.97	849	.424	7.41	2.945	1.51	2	86.3	40	<.5	6.6	9.8	1.0	1	28	10	3.03	83	2
B 172033	2.5	164	7	182	.2	67	44	425	7.17	4	3	<4	1	99	1.2	2	2	296	1.85	.223	17	38	.91	357	.375	7.31	.321	2.71	4	55.3	37	.7	6.7	6.2	.5	2	26	8	4.03	139	1
STANDARD CT3	26.3	60	38	182	5.7	38	12	1007	4.18	63	25	<4	26	234	21.4	23	24	136	1.59	.095	28	259	.95	1078	.384	7.16	1.908	1.76	28	54.5	46	20.1	12.6	17.2	<.5	5	12	35	.03	75	<1
STANDARD G-2	1.6	<1	20	51	<.2	7	4	796	2.57	<2	5	<4	8	796	<.2	6	2	59	3.09	.090	30	71	.74	1050	.246	8.51	2.732	2.67	2	13.5	48	.8	12.8	15.7	1.1	3	8	36	<.01	138	<1

GROUP 1EX - 0.25 GM SAMPLE DIGESTED WITH HCLO4-HNO3-HCL-HF TO 10 ML. UPPER LIMITS - AG, AU, W = 200 PPM; MO, CO, CD, SB, BI, TH & U = 4,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM. DIGESTION IS PARTIAL FOR SOME MINERALS & MAY VOLATIZE SOME ELEMENTS, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: CORE REJ. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUL 20 2000 DATE REPORT MAILED: July 27/00 SIGNED BY: C. Leong D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data h FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003016R Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0751	2.8	55	13	101	.2	57	16	663	3.15	65	2	<2	4	145	1.0	2.4	<.5	17	4.20	.086	6	11	1.44	117	.004	9	.38	.020	.16	2	<1	3.7	<1	.68	1
0752	6.8	57	36	142	.3	64	15	791	3.37	73	2	<2	4	140	1.6	2.2	<.5	24	4.53	.094	8	17	1.79	159	.006	7	.50	.030	.22	3	<1	3.9	<1	.50	1
0753	3.1	82	13	177	.3	55	28	1438	6.86	53	<1	<2	5	40	.4	1.1	.5	12	.82	.067	11	14	1.40	81	.003	10	.56	.022	.19	1	<1	6.4	<1	.54	1
0754	5.8	48	25	127	.4	64	18	1417	4.27	136	2	<2	4	186	1.4	2.3	.8	42	4.63	.117	7	18	1.85	97	.002	11	.51	.014	.17	3	<1	7.7	<1	.95	1
0755	4.5	10	5	31	.2	68	12	1100	4.09	200	2	<2	5	293	.8	<.5	.6	37	4.45	.322	5	17	1.49	130	.003	14	.49	.016	.24	3	<1	4.7	<1	2.48	1
0756	2.9	21	4	63	.3	186	65	2326	7.32	487	2	<2	<1	479	<.2	.6	.5	27	8.54	.172	3	47	3.35	95	.033	9	.65	.026	.33	2	<1	13.2	<1	1.58	1
0757	1.2	56	4	79	.3	140	40	2474	7.44	329	2	<2	<1	447	<.2	.7	.9	25	9.01	.130	2	29	3.91	103	.027	6	.53	.020	.26	2	<1	11.9	<1	1.45	1
0758	4.9	22	4	25	.1	69	18	1266	4.12	209	2	<2	2	208	.7	.6	<.5	29	3.60	.136	6	22	1.28	144	.004	13	.52	.015	.25	6	<1	6.0	<1	1.72	1
0759	2.8	15	149	42	4.4	284	139	3261	19.79	1104	1	24	1	149	<.2	4.1	14.3	24	4.51	.131	2	25	1.80	76	.037	7	.54	.010	.31	11	1	10.9	<1	16.72	<1
0760	2.3	16	42	41	2.1	160	58	3580	8.46	516	1	14	<1	210	<.2	.9	3.1	26	7.91	.130	3	30	3.01	101	.042	12	.68	.015	.36	3	1	10.3	<1	4.73	2
0761	1.8	8	19	53	1.0	130	39	4758	9.73	461	<1	6	<1	303	.2	<.5	1.8	20	9.61	.104	2	18	3.89	75	.027	3	.42	.012	.25	3	2	11.7	1	3.74	<1
0762	2.9	10	17	48	.4	129	46	2489	8.07	340	1	<2	<1	192	<.2	<.5	3.9	14	8.03	.117	1	15	3.07	69	.018	3	.25	.007	.14	2	<1	7.2	<1	4.12	<1
0763	2.5	12	89	28	2.5	309	79	367	19.33	1296	<1	11	2	39	<.2	<.5	26.2	11	1.06	.019	2	18	.47	69	.013	10	.39	.010	.21	4	<1	2.8	<1	18.00	1
0764	3.6	16	27	58	.5	206	64	1607	11.96	654	1	2	<1	138	<.2	1.0	9.6	19	5.93	.039	1	33	2.50	129	.025	6	.57	.013	.32	4	<1	9.3	<1	6.97	<1
0765	2.7	20	64	36	2.8	294	91	1276	16.25	1102	1	20	17	209	<.2	<.5	7.6	17	3.61	.113	3	32	1.79	93	.024	9	.53	.012	.28	3	<1	8.1	<1	13.80	1
RE 0765	3.0	21	67	36	2.8	303	94	1335	16.83	1149	1	21	17	221	<.2	<.5	8.1	19	3.73	.116	3	32	1.85	97	.024	12	.56	.011	.29	3	<1	8.5	<1	14.36	1
0766	2.4	16	16	43	.6	197	67	2570	10.61	714	1	5	17	292	<.2	.6	2.6	21	7.52	.200	4	33	2.95	152	.037	9	.74	.019	.37	3	1	10.7	<1	6.12	2
0767	.9	16	7	52	.3	82	34	2536	6.38	231	1	<2	<1	502	.9	<.5	<.5	21	10.49	.100	2	24	4.19	145	.015	5	.50	.013	.29	2	<1	12.3	<1	1.68	1
0768	2.3	73	9	99	.3	88	38	330	8.42	253	1	<2	<1	95	.4	1.5	1.1	27	1.70	.297	3	19	.52	145	.025	8	.79	.019	.40	3	5	5.1	3	8.16	3
0769	5.5	59	11	95	.3	80	40	200	7.10	152	2	<2	1	107	1.0	1.5	1.5	20	1.40	.438	4	12	.33	99	.011	7	.63	.016	.32	3	2	4.3	<1	7.29	3
0771	4.0	98	6	204	.2	56	49	437	7.55	84	1	<2	1	57	.9	.6	<.5	27	.82	.295	5	14	.37	129	.027	6	.80	.019	.39	3	2	4.4	<1	6.00	2
0772	1.6	105	5	116	.3	52	44	712	9.01	83	<1	<2	1	57	.6	<.5	<.5	20	.73	.214	4	8	.73	103	.017	4	.57	.020	.26	3	2	4.7	<1	4.65	1
0773	5.3	83	7	144	.2	54	49	577	10.03	72	<1	<2	1	70	.7	.6	1.1	19	1.04	.233	4	9	.62	107	.019	2	.58	.023	.27	2	3	4.3	2	7.00	2
0774	2.0	190	6	134	.3	100	77	640	9.01	206	<1	<2	1	46	1.2	2.3	.5	24	.92	.207	5	14	.49	101	.025	4	.56	.042	.25	4	7	4.3	<1	6.38	2
0775	1.4	188	4	100	.2	80	62	1580	8.66	164	<1	<2	1	41	.7	.5	<.5	34	.92	.240	8	9	.94	200	.026	6	.70	.080	.28	1	8	6.2	<1	1.50	2
0776	.8	163	3	73	.1	65	51	792	5.85	86	1	<2	1	40	.4	.6	<.5	23	.94	.230	6	7	.64	184	.021	6	.58	.072	.24	1	1	5.0	<1	1.89	2
0777	1.8	148	4	102	.1	73	49	719	7.75	71	<1	<2	1	53	.4	1.5	<.5	29	1.25	.176	4	11	.74	132	.031	7	.71	.092	.27	2	2	6.2	1	4.74	2
0778	1.6	67	7	105	.5	67	33	1721	8.93	451	<1	<2	<1	312	<.2	1.0	.8	22	3.83	.156	2	9	1.48	118	.019	8	.60	.053	.30	1	1	11.7	<1	6.28	1
0779	2.7	55	19	102	.8	92	82	1379	17.50	802	<1	<2	1	267	<.2	2.5	2.4	34	2.40	.177	2	11	1.28	123	.063	9	.89	.025	.43	2	3	11.4	<1	16.16	2
0780	4.7	57	13	73	.7	95	75	1505	12.74	754	<1	<2	1	263	<.2	.9	1.9	31	2.58	.198	3	9	1.11	126	.049	8	.80	.027	.39	2	1	11.7	<1	11.80	2
0781	2.1	30	10	64	.7	71	58	2029	12.28	389	<1	<2	2	167	<.2	1.0	1.9	39	1.83	.260	4	12	1.15	135	.047	7	.90	.052	.41	2	<1	10.1	<1	7.52	2
0782	.8	23	3	73	.4	114	88	2659	10.16	305	<1	<2	1	194	<.2	<.5	.5	40	2.08	.246	4	5	1.86	196	.041	10	.80	.044	.38	1	1	13.8	<1	2.93	2
0783	1.4	46	18	59	1.2	154	97	2030	12.74	322	<1	3	<1	202	<.2	1.9	1.9	37	2.80	.193	3	11	1.63	179	.056	10	.86	.046	.39	2	1	13.9	<1	7.06	2
0784	.5	12	3	47	.3	98	41	1896	7.24	187	1	<2	<1	254	.6	<.5	1.0	28	4.40	.163	2	17	1.95	235	.047	11	.77	.050	.36	1	1	12.4	<1	1.85	2
0785	.8	11	4	50	.4	64	48	1712	7.62	138	<1	<2	1	186	.5	<.5	<.5	45	2.78	.239	3	9	1.43	278	.078	9	.96	.061	.45	1	<1	11.9	<1	1.87	3
STANDARD C3	27.0	67	39	166	5.3	37	12	814	3.34	57	24	<2	21	30	25.2	16.5	22.7	83	.61	.095	18	177	.63	160	.086	23	1.83	.048	.18	15	1	4.4	<1	.03	8
STANDARD G-2	1.6	2	2	42	<.1	7	4	552	2.07	1	3	<2	5	87	<.2	<.5	<.5	43	.71	.101	8	82	.62	255	.132	<1	1.10	.146	.60	2	<1	2.5	<1	<.01	6

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 2 2000 DATE REPORT MAILED: Oct 10/00 SIGNED BY: ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0786	1.5	21	8	30	.4	99	57	1253	7.04	183	<1	<2	1	258	.7	1.8	2.0	19	5.11	.223	2	7	1.49	149	.001	4	.44	.028	.22	1	1	11.3	<1	4.38	2
0787	1.7	40	17	48	.9	146	94	1519	11.55	312	1	2	2	282	.4	3.6	4.2	18	4.63	.161	2	13	1.71	65	.001	5	.41	.024	.23	1	2	13.2	<1	8.29	1
0788	2.1	26	13	62	.9	69	44	1869	9.72	162	1	3	3	207	.6	<.5	2.1	21	3.46	.194	2	5	1.73	86	.001	4	.37	.027	.20	1	<1	12.3	<1	4.31	1
0789	5.2	88	48	136	2.8	101	96	477	22.54	397	<1	7	2	113	.3	1.0	6.4	15	1.58	.193	2	12	.53	36	.002	5	.38	.023	.18	2	5	7.6	2	24.00	1
0790	4.1	115	46	171	2.8	150	85	65	25.71	515	<1	8	3	64	.2	2.2	6.1	8	.64	.194	2	8	.08	33	.002	11	.28	.016	.14	2	5	2.8	3	29.00	<1
0792	2.5	45	21	63	1.2	60	56	983	10.57	199	1	3	1	215	.8	1.0	3.4	19	3.85	.250	2	7	1.08	62	.001	5	.42	.024	.20	1	1	10.4	2	9.10	2
0793	6.0	70	61	114	3.9	111	73	396	17.51	368	1	10	1	91	.2	2.9	7.3	19	1.58	.193	3	13	.43	35	.002	10	.45	.032	.21	2	2	5.8	2	17.41	1
0794	1.5	35	11	122	.6	88	66	1750	10.75	346	<1	<2	2	177	.2	1.5	2.5	24	2.57	.236	4	7	1.22	67	.001	3	.43	.037	.23	1	1	9.6	2	6.62	1
0795	2.7	36	36	52	2.4	92	73	846	13.48	413	1	15	2	202	<.2	2.2	5.4	17	2.96	.310	3	8	.87	48	.001	4	.50	.022	.28	2	2	8.2	2	12.92	2
0796	1.8	45	61	83	3.8	72	65	875	20.60	529	2	29	1	198	<.2	.7	7.6	14	2.61	.226	3	7	1.03	58	.001	7	.32	.012	.20	1	2	7.4	1	23.00	1
0797	1.2	7	11	17	.4	40	45	756	4.74	167	<1	2	3	202	.6	<.5	1.5	22	3.18	.394	4	4	.86	123	.002	7	.57	.019	.31	1	1	8.6	1	3.52	3
0798	1.2	14	17	22	.7	57	62	690	7.09	242	<1	4	2	224	<.2	<.5	3.2	24	3.57	.501	5	5	.80	65	.002	4	.57	.020	.32	1	1	8.9	<1	5.95	2
0799	1.6	19	7	59	.3	57	54	1333	9.85	152	<1	<2	1	142	.5	<.5	2.1	25	2.42	.336	4	7	1.28	86	.001	3	.62	.031	.26	1	1	9.3	1	4.88	1
0800	2.2	20	4	72	.2	78	56	2004	11.17	124	<1	<2	4	149	.4	<.5	1.4	25	3.28	.221	4	5	2.11	84	.001	<1	.36	.028	.16	1	<1	11.6	<1	3.05	1
0801	2.6	76	23	46	.9	85	86	801	14.07	254	1	4	3	106	<.2	3.5	4.9	25	1.81	.236	4	10	.77	49	.002	3	.48	.041	.19	2	3	9.7	2	12.58	2
0802	1.4	50	8	65	.2	69	61	1415	10.95	118	<1	<2	3	107	.4	1.1	3.0	24	1.70	.270	4	6	1.24	75	.001	4	.47	.035	.20	1	1	10.2	2	5.99	1
0803	1.4	18	3	52	.2	47	46	1896	8.04	119	1	<2	2	222	.4	<.5	1.2	26	4.32	.259	3	4	1.95	137	.001	2	.59	.023	.21	1	<1	11.3	<1	1.83	2
0804	1.3	74	3	78	.2	68	52	1562	8.48	102	1	<2	3	119	.4	<.5	<.5	21	3.02	.171	3	7	1.90	130	.001	2	.54	.017	.18	1	<1	9.0	<1	1.61	1
0805	1.0	154	3	61	.2	80	51	1268	8.28	72	<1	<2	2	82	.3	<.5	<.5	14	2.20	.147	2	9	1.44	125	.001	6	.35	.016	.18	1	1	5.4	<1	2.69	1
RE 0805	1.0	152	3	59	.1	84	49	1272	8.30	67	<1	<2	3	83	.3	<.5	<.5	12	2.18	.148	2	9	1.44	126	.001	<1	.36	.015	.18	1	1	5.6	<1	2.67	1
0806	1.6	103	2	43	.2	59	42	1759	6.50	111	<1	<2	2	107	.4	<.5	.5	22	3.10	.239	5	6	1.33	116	.002	2	.49	.020	.28	1	<1	5.9	<1	1.64	1
0807	2.3	12	10	14	.1	68	34	494	5.18	189	4	<2	14	38	.6	<.5	2.6	4	.89	.076	6	5	.28	55	<.001	5	.33	.011	.22	1	2	2.4	2	5.28	1
0808	2.0	15	5	10	.1	44	24	658	3.82	223	3	<2	11	47	.7	<.5	<.5	6	1.08	.080	6	8	.37	75	.001	6	.41	.012	.25	1	<1	2.6	<1	3.64	2
0809	3.8	25	4	13	.2	62	23	1201	3.18	232	1	<2	6	75	<.2	<.5	<.5	8	2.08	.070	5	10	.78	64	.001	4	.31	.013	.19	2	<1	3.1	<1	2.25	1
0810	1.9	44	5	41	.1	34	14	228	3.32	98	2	<2	8	14	.5	<.5	<.5	6	.15	.041	10	11	.31	70	.001	5	.32	.011	.18	3	<1	1.1	<1	2.30	1
STANDARD C3	27.1	69	38	172	5.7	39	12	834	3.48	61	24	<2	19	30	25.7	15.4	23.9	85	.62	.098	19	176	.66	160	.093	22	1.87	.046	.18	15	1	4.5	<1	.03	9
STANDARD G-2	1.6	2	3	43	<.1	8	4	557	2.05	<1	2	<2	3	73	<.2	<.5	<.5	44	.68	.108	7	79	.64	239	.133	4	.95	.088	.52	2	<1	2.7	<1	.01	6

Sample type: CORE PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. File # A002860R Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0660	.4	26	10	29	.1	65	20	1795	3.63	127	2	<2	2	201	.7	.6	<.5	12	6.84	.084	3	10	2.54	58	.001	4	.28	.009	.19	1	<1	5.9	<1	.30	1
0661	1.0	85	8	69	.2	79	35	1336	5.36	122	1	<2	<1	136	.6	2.2	<.5	15	5.03	.127	2	6	2.53	57	.002	8	.30	.009	.20	1	<1	5.4	<1	.97	1
0662	1.2	90	6	85	.3	141	56	1838	6.83	167	1	<2	<1	145	.7	7.1	<.5	18	5.58	.120	2	11	3.31	79	.003	5	.32	.008	.21	5	<1	6.2	<1	2.21	1
0663	1.7	61	3	71	.2	155	31	1574	6.51	155	<1	<2	<1	169	.6	2.0	<.5	14	6.34	.119	1	21	4.00	54	.002	2	.26	.008	.18	1	<1	6.6	<1	.75	<1
0664	1.6	73	4	49	.2	52	27	989	4.59	62	1	<2	1	116	.3	1.2	1.1	12	4.48	.106	3	8	1.75	82	.002	7	.33	.009	.21	1	<1	4.0	<1	1.26	1
0665	2.2	65	3	56	.2	92	31	930	4.94	64	1	<2	<1	177	.3	.5	<.5	10	7.40	.108	2	10	2.17	94	.001	4	.26	.008	.17	1	<1	5.9	<1	1.26	1
0666	1.9	83	4	74	.2	161	33	880	4.63	66	1	<2	<1	204	.5	.9	<.5	10	7.57	.077	2	16	2.49	104	.002	8	.29	.013	.16	<1	<1	6.4	<1	.82	<1
0667	2.2	46	4	49	.1	49	16	588	3.06	26	2	<2	4	164	.2	.5	<.5	6	6.10	.046	3	8	1.50	119	.001	3	.24	.011	.15	1	<1	3.8	<1	.62	1
0668	6.4	85	7	63	.3	59	39	982	7.40	39	1	<2	1	162	.3	2.0	<.5	17	6.14	.175	2	6	1.64	82	.003	8	.37	.012	.20	1	<1	5.9	<1	3.77	1
0669	3.8	72	6	74	.2	51	38	1201	7.33	93	<1	<2	1	131	.5	.6	<.5	16	3.76	.134	2	5	1.40	73	.003	3	.35	.009	.22	1	<1	5.0	<1	4.20	1
0670	1.6	20	<2	20	<.1	15	5	577	1.87	21	1	<2	5	80	<.2	<.5	<.5	3	1.86	.022	9	10	.75	110	.001	4	.27	.010	.18	2	<1	1.5	<1	.25	1
0674	6.2	47	13	48	.4	72	44	1414	8.64	199	1	<2	1	170	.8	1.1	2.2	17	5.28	.169	1	4	1.57	81	.003	1	.32	.008	.21	1	<1	6.2	<1	5.42	1
0675	4.1	21	118	38	2.1	315	158	1559	19.74	1185	1	18	2	82	<.2	.6	10.4	13	1.80	.091	1	6	1.04	42	.002	6	.25	.003	.17	1	<1	4.9	<1	19.68	<1
0676	3.4	5	10	37	.3	42	7	3702	4.76	78	2	<2	<1	274	.4	.6	1.0	15	8.14	.090	2	3	2.96	68	.002	4	.27	.010	.19	<1	2	9.2	2	.80	<1
0677	.8	<1	2	8	<.1	9	1	1210	1.18	17	1	<2	9	65	<.2	<.5	<.5	6	1.85	.067	19	4	.66	61	.001	3	.37	.010	.24	<1	<1	3.7	<1	.08	2
0678	1.9	4	5	16	.1	52	14	2503	2.64	100	2	<2	4	148	.4	<.5	<.5	9	4.57	.075	7	7	1.60	69	.001	3	.31	.011	.21	<1	<1	5.5	1	.37	1
0679	2.7	5	47	20	1.7	157	55	1030	9.23	622	1	18	60	101	<.2	<.5	6.6	10	2.54	.090	2	10	1.01	76	.002	6	.38	.011	.24	2	<1	3.2	<1	8.99	1
0680	1.3	67	12	35	.2	121	42	1211	5.20	317	2	<2	1	197	<.2	.6	.9	12	4.78	.100	1	14	1.92	124	.001	1	.29	.009	.19	1	1	5.5	<1	2.82	1
RE 0680	1.3	72	12	36	.2	127	45	1241	5.24	321	2	<2	<1	203	<.2	1.1	1.1	13	4.90	.103	1	15	1.97	133	.001	3	.31	.010	.20	1	1	5.7	<1	2.83	2
0681	2.9	103	18	60	.2	54	33	304	8.64	135	<1	<2	1	50	.7	3.0	.8	19	.89	.279	2	11	.28	41	.003	3	.51	.017	.29	2	11	2.6	2	9.08	2
0682	5.2	25	112	44	2.1	289	113	683	17.72	1098	1	15	<1	59	.2	1.7	19.0	17	1.29	.403	3	9	.31	39	.003	12	.45	.013	.25	2	5	3.4	1	18.00	2
0683	4.6	37	11	69	.3	71	48	422	9.30	131	<1	<2	1	55	.7	1.5	2.1	14	1.10	.313	3	10	.39	48	.002	8	.54	.016	.31	2	8	2.4	2	9.74	2
0684	4.5	16	23	58	.4	85	54	419	8.12	178	<1	2	1	67	.8	1.0	3.7	12	1.37	.316	2	7	.32	51	.002	5	.46	.013	.27	1	3	2.7	2	8.58	1
0685	6.2	25	243	47	2.7	401	158	228	18.82	1197	1	24	1	43	<.2	1.0	15.6	12	.85	.289	2	8	.13	42	.003	12	.44	.010	.25	2	2	2.0	<1	21.19	1
0686	11.0	43	311	52	5.9	460	177	497	21.79	1284	<1	65	1	54	.2	.6	16.9	12	.81	.239	2	6	.29	41	.004	12	.35	.008	.21	2	5	2.8	1	22.53	1
0687	2.4	52	183	57	3.9	355	144	356	20.49	1212	1	46	1	35	<.2	<.5	10.4	19	.71	.248	2	9	.13	27	.004	9	.45	.010	.27	3	2	3.1	<1	23.00	1
0688	1.6	98	240	38	3.6	311	118	361	20.94	1254	<1	28	2	38	<.2	.5	12.2	13	.75	.165	2	5	.17	48	.003	5	.32	.008	.21	3	1	2.7	<1	23.00	1
0689	2.9	51	258	54	6.5	372	141	611	25.28	1509	<1	59	2	65	.3	<.5	19.9	13	1.11	.167	2	9	.36	39	.003	4	.33	.007	.20	2	3	3.8	<1	24.54	<1
0690	2.4	46	38	80	.9	89	62	753	12.50	498	<1	3	2	155	.4	.9	7.1	18	2.41	.289	3	5	.77	57	.003	8	.43	.011	.27	2	4	8.9	<1	12.00	1
0691	2.5	46	61	110	1.4	93	62	249	12.24	288	<1	7	2	89	.3	.7	8.5	19	1.23	.346	3	7	.27	35	.003	7	.53	.016	.30	6	4	6.1	1	12.00	2
0692	1.3	15	7	32	.2	36	45	1095	4.73	122	2	<2	2	253	.5	.8	1.2	24	4.65	.401	3	5	1.26	98	.003	7	.59	.019	.32	2	9	11.4	<1	2.77	3
0693	1.1	32	10	49	.2	89	69	1710	8.82	500	<1	<2	1	137	<.2	<.5	2.2	13	2.95	.258	3	4	1.14	100	.002	6	.42	.015	.26	1	8	7.3	<1	5.54	2
0697	.9	131	3	38	.1	56	45	864	4.92	97	<1	<2	1	38	.3	<.5	.7	15	.79	.260	6	3	.46	104	.002	7	.39	.014	.23	1	1	3.5	<1	1.23	1
0698	1.0	91	7	79	.1	59	46	1361	7.24	46	<1	<2	2	35	.2	<.5	<.5	21	.77	.226	8	5	.80	139	.001	3	.44	.035	.22	<1	1	5.6	<1	.51	2
0699	.8	163	3	68	.1	57	48	964	5.58	72	<1	<2	2	38	.3	.7	<.5	18	.92	.226	6	4	.60	115	.001	7	.38	.031	.19	<1	1	4.1	<1	1.31	2
STANDARD C3	26.5	67	35	170	5.3	38	12	781	3.37	59	24	<2	21	29	25.2	16.3	22.8	80	.59	.095	18	177	.60	160	.086	21	1.85	.042	.17	14	1	4.4	<1	.04	8
STANDARD G-2	1.4	2	2	40	<.1	7	4	477	1.82	<1	2	<2	3	67	<.2	<.5	<.5	37	.59	.093	7	73	.54	214	.113	6	.83	.074	.45	2	<1	2.3	<1	<.01	6

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 2 2000 DATE REPORT MAILED: Oct 14/00 SIGNED BY: D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0700	3.4	187	7	66	.2	85	70	669	10.31	119	<1	<2	1	36	.6	1.5	<.5	21	.94	.231	4	7	.33	41	.002	2	.46	.016	.28	1	7	3.3	<1	8.17	1
0701	1.4	88	10	48	.2	77	56	1089	7.73	331	<1	<2	1	113	<.2	<.5	1.3	21	2.04	.290	4	4	.74	66	.002	5	.52	.017	.31	1	2	6.3	<1	5.40	2
0702	1.6	209	4	150	.1	85	62	1552	9.17	158	<1	<2	2	33	.7	1.3	<.5	16	.82	.167	3	8	.96	63	.001	5	.49	.019	.28	1	1	4.8	<1	3.81	1
0703	1.0	175	3	158	.1	80	49	1655	9.17	118	<1	<2	1	38	.6	1.1	<.5	14	1.00	.160	3	7	1.16	116	.001	4	.40	.020	.23	<1	<1	5.1	<1	2.32	1
0704	1.1	154	3	114	.1	88	48	1209	8.42	134	<1	<2	1	45	.5	.9	<.5	15	1.21	.161	3	8	.94	75	.001	2	.43	.021	.25	1	1	4.7	2	2.76	1
0705	1.7	134	7	90	.2	79	53	1387	10.92	148	<1	<2	1	60	.5	1.9	<.5	16	1.50	.156	2	9	.99	56	.001	1	.42	.017	.24	1	1	5.9	2	5.48	<1
0706	1.4	113	3	81	.1	68	45	1442	8.11	118	<1	<2	1	54	.4	.5	<.5	15	1.47	.144	3	6	1.07	98	.001	2	.36	.016	.22	1	<1	5.8	<1	1.81	1
0707	1.7	92	4	78	.1	49	41	846	6.80	78	<1	<2	2	57	.3	<.5	.8	23	1.15	.251	4	7	.82	66	.001	5	.50	.024	.24	1	2	5.9	<1	2.36	2
0708	1.8	92	<2	125	.1	33	29	1349	7.55	16	<1	<2	2	51	.2	<.5	<.5	18	1.11	.156	5	4	1.33	177	.001	2	.32	.019	.17	<1	<1	6.2	<1	.74	1
0709	3.0	143	3	105	.1	53	45	963	7.39	31	<1	<2	<1	53	.2	.5	<.5	19	1.02	.322	5	8	.75	45	.002	5	.46	.034	.22	1	1	5.2	<1	3.06	2
0710	2.4	155	3	94	.1	52	50	1177	7.65	36	<1	<2	1	50	<.2	1.2	<.5	18	1.13	.240	5	5	.94	114	.001	2	.36	.026	.19	1	2	5.3	<1	2.25	1
0711	2.7	187	6	95	.1	66	59	933	12.68	95	1	<2	1	45	.4	2.4	<.5	19	1.10	.204	4	8	.66	31	.001	5	.40	.027	.20	1	3	5.5	4	9.50	1
0712	2.5	83	4	69	.1	45	37	1174	7.33	73	<1	<2	1	59	.3	<.5	<.5	16	1.26	.272	5	9	.87	48	.001	5	.54	.027	.26	1	<1	5.3	<1	3.09	2
0713	1.9	105	7	54	.2	47	53	795	11.52	69	<1	<2	1	53	.2	1.7	<.5	14	1.29	.257	3	9	.64	37	.001	2	.42	.025	.22	2	2	4.0	2	9.25	1
0714	1.7	60	3	71	<.1	41	37	1278	7.20	53	<1	<2	2	45	.2	<.5	<.5	12	.95	.310	4	8	.96	95	.001	4	.49	.026	.24	<1	<1	4.1	<1	2.14	2
0715	.9	91	3	78	.1	35	31	1389	7.80	52	<1	<2	1	48	.2	<.5	<.5	11	1.01	.306	5	6	1.08	87	.001	3	.45	.028	.22	1	<1	4.3	<1	1.82	1
0716	1.4	66	<2	75	.1	33	26	1458	6.60	60	<1	<2	<1	81	.3	<.5	<.5	14	1.75	.288	5	6	1.30	187	.001	3	.47	.023	.24	1	<1	5.2	<1	.61	1
RE 0716	1.4	68	<2	77	.1	33	26	1442	6.74	60	<1	<2	2	81	.3	<.5	<.5	12	1.73	.284	6	7	1.29	188	.001	5	.48	.022	.24	<1	<1	5.2	<1	.60	2
0720	2.5	153	5	111	.1	65	52	1086	11.52	106	1	<2	2	31	.5	1.8	<.5	18	.72	.195	3	7	.79	40	.001	1	.33	.024	.17	<1	2	4.8	1	7.00	2
0721	.9	105	3	123	.1	62	54	1675	10.42	123	<1	<2	1	44	.5	<.5	<.5	20	.92	.187	4	4	1.21	68	.001	1	.33	.024	.15	<1	<1	8.0	<1	2.94	1
0722	2.1	141	3	100	.1	59	47	1465	10.49	95	<1	<2	1	44	.4	1.7	<.5	18	1.12	.203	4	6	1.08	54	.001	1	.38	.028	.19	<1	1	5.7	<1	4.15	1
0723	1.3	171	5	80	.1	72	57	698	10.17	108	<1	<2	2	47	.4	2.4	<.5	19	1.07	.220	4	6	.68	39	.001	6	.39	.032	.20	1	1	4.9	1	6.77	1
0724	1.2	163	<2	105	.1	42	37	1456	7.56	84	1	<2	2	63	.3	.5	<.5	14	1.53	.140	3	4	1.49	125	.001	3	.33	.026	.17	<1	<1	5.4	<1	.81	1
0725	3.0	70	8	71	.2	39	37	1071	12.73	73	1	<2	<1	185	.5	3.8	<.5	16	5.54	.092	2	5	1.85	67	.001	<1	.21	.018	.11	1	2	5.1	2	8.69	<1
0726	1.8	103	2	95	.2	43	31	1201	7.69	47	<1	<2	1	108	.2	.6	<.5	18	2.97	.177	3	5	1.62	107	.001	4	.32	.036	.16	<1	<1	6.1	<1	1.75	1
0727	1.5	109	6	83	.2	73	51	613	11.15	101	<1	<2	<1	107	.4	2.2	<.5	15	2.82	.140	2	8	1.13	57	.001	<1	.31	.033	.16	1	4	4.3	2	8.69	1
0728	2.2	129	6	81	.2	95	55	1098	10.69	162	<1	<2	1	103	.7	1.7	<.5	14	2.53	.157	2	9	1.43	67	.001	<1	.38	.023	.19	<1	4	5.3	<1	5.92	1
STANDARD C3	26.3	67	37	173	5.4	37	12	800	3.49	58	24	<2	20	29	23.2	15.3	23.1	79	.60	.097	18	175	.63	163	.087	21	1.81	.042	.17	14	1	4.4	<1	.03	9
STANDARD G-2	1.4	3	2	44	<.1	7	4	529	2.02	<1	2	<2	4	72	<.2	<.5	<.5	41	.65	.101	7	75	.61	228	.127	1	.91	.080	.50	2	<1	2.5	<1	<.01	5

Sample type: CORE PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002724R

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: R. Hall

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0560	.8	11	16	37	.3	55	30	3434	7.53	174	1	<2	3	285	.7	1.1	<.5	13	8.19	.109	3	7	3.19	95	.001	9	.64	.015	.28	1	<1	7.5	<1	1.16	2
0561	.9	12	7	47	.3	153	39	4235	8.65	362	2	<2	1	358	<.2	2.3	.7	14	12.21	.095	1	23	5.65	64	.003	5	.51	.009	.21	2	1	8.4	<1	1.26	1
0562	2.9	7	24	44	.8	127	52	6394	19.48	485	1	4	1	285	<.2	.8	4.3	19	12.81	.121	2	10	6.44	84	.002	4	.83	.013	.27	1	1	10.3	1	4.55	<1
0563	1.5	12	5	25	.2	27	10	2814	3.63	109	1	<2	6	110	.3	<.5	<.5	8	3.84	.063	8	6	1.48	75	.001	3	.46	.013	.26	1	<1	5.3	1	.85	1
0564	3.4	40	4	24	<.1	32	11	433	2.95	68	1	<2	5	23	.2	<.5	<.5	3	.55	.036	11	16	.67	105	.001	4	.34	.012	.22	1	<1	1.6	<1	.90	2
0565	.9	46	4	27	<.1	29	10	476	2.68	71	1	<2	5	30	.2	<.5	<.5	3	.72	.033	11	12	.65	105	.001	2	.30	.015	.21	5	<1	1.5	<1	.81	1
0566	3.2	94	5	134	.1	90	28	813	5.34	183	1	<2	2	56	1.0	<.5	<.5	10	1.52	.139	8	23	1.45	147	.003	8	.57	.017	.29	1	<1	3.2	<1	1.42	2
0567	1.1	88	3	97	.2	154	39	918	8.20	34	1	<2	<1	154	<.2	<.5	<.5	16	5.40	.098	3	35	3.09	128	.001	5	.57	.018	.22	2	<1	6.6	<1	.94	2
0568	2.8	75	3	91	.2	123	37	941	9.05	13	1	<2	10	169	<.2	<.5	<.5	15	5.44	.146	4	28	2.93	191	.004	6	.70	.021	.27	<1	<1	5.4	<1	1.33	2
0569	1.0	103	4	58	.1	135	45	577	4.40	28	<1	<2	<1	106	<.2	<.5	<.5	13	2.23	.141	2	23	1.34	243	.002	5	.55	.018	.27	2	<1	5.3	<1	1.34	2
0570	4.3	105	14	200	.3	66	50	413	8.78	53	<1	<2	<1	152	.8	2.9	<.5	19	3.88	.229	3	13	1.38	59	.002	5	.70	.018	.28	<1	1	6.2	1	4.31	2
0572	5.1	106	11	191	.2	71	43	183	8.57	89	<1	<2	1	72	1.1	3.3	<.5	25	1.65	.289	3	17	.45	36	.002	5	.80	.018	.29	1	8	4.5	5	7.01	2
0573	4.4	79	8	133	.2	61	43	478	8.89	95	<1	<2	1	61	.7	2.5	1.1	18	1.28	.292	5	16	.57	47	.002	5	.85	.019	.34	2	9	3.4	4	6.44	2
0574	2.1	57	10	117	.3	71	63	639	10.48	138	<1	<2	2	119	.9	1.1	2.0	26	2.07	.423	6	8	.69	49	.002	7	1.12	.019	.35	2	3	6.2	1	6.27	3
RE 0574	2.2	59	10	121	.3	71	63	649	10.65	142	<1	<2	2	121	.9	.5	1.9	26	2.10	.424	6	8	.70	46	.002	7	1.14	.019	.36	2	3	6.3	2	6.34	2
0576	1.7	40	13	83	.4	69	67	1153	13.21	216	<1	<2	2	156	.9	1.6	2.7	32	3.31	.375	5	5	1.22	28	.003	7	1.24	.022	.36	2	9	10.5	<1	7.09	2
0577	3.0	55	20	99	1.0	85	82	1140	14.45	276	<1	7	2	142	<.2	3.3	4.0	30	3.05	.339	4	7	1.22	46	.003	10	1.05	.016	.34	1	14	9.0	2	8.84	2
0578	2.2	91	15	185	.4	68	59	838	12.46	172	<1	<2	1	145	1.1	2.6	2.4	29	2.67	.325	5	6	.91	46	.004	7	.95	.025	.35	2	12	7.0	1	7.34	2
0579	2.9	91	8	87	.2	97	81	1248	12.33	151	<1	<2	1	105	.7	2.3	2.3	29	2.30	.300	6	8	1.22	52	.002	5	.85	.038	.31	1	8	7.6	1	5.43	2
0580	1.2	27	5	85	.1	80	74	1852	10.45	138	<1	<2	2	84	.5	<.5	1.3	32	1.74	.312	7	5	1.66	76	.002	8	.89	.040	.32	1	3	9.4	<1	3.44	3
0581	2.8	28	7	71	.2	55	59	1339	10.14	107	<1	<2	2	141	.4	.6	2.0	30	2.90	.338	5	6	1.43	89	.002	6	.83	.034	.32	1	3	9.0	1	3.24	2
0582	1.9	60	7	114	.2	73	72	1749	13.85	143	<1	<2	1	120	.6	1.5	1.9	31	2.76	.314	5	6	1.64	58	.002	5	.86	.035	.30	1	6	10.1	<1	4.97	2
0583	3.3	150	4	137	.1	63	52	967	7.96	111	<1	<2	2	55	.5	.9	.6	23	1.08	.267	6	11	.74	50	.002	5	.77	.035	.27	1	2	5.5	<1	3.30	2
0584	2.2	57	7	99	.1	64	50	922	8.68	188	<1	<2	1	47	.9	<.5	1.9	22	1.15	.256	4	8	.60	51	.002	6	.74	.019	.31	3	3	3.8	<1	5.53	2
0585	2.8	91	10	81	.2	81	68	1726	12.34	383	1	<2	1	61	<.2	.8	1.9	26	1.55	.244	5	10	1.04	61	.004	7	.93	.021	.37	1	3	5.4	<1	5.80	1
0586	1.3	29	17	36	.5	97	72	2840	14.40	611	2	<2	1	264	<.2	1.3	4.7	25	7.61	.275	3	6	2.52	85	.005	10	1.14	.020	.36	2	2	11.1	<1	7.89	1
0587	2.1	46	17	32	.4	94	76	2058	14.42	711	2	<2	1	197	<.2	<.5	4.8	26	5.21	.276	3	7	1.86	52	.002	7	1.00	.018	.34	1	2	10.4	<1	8.73	2
0588	.9	70	4	59	.1	59	47	1111	7.39	227	1	<2	2	80	.7	<.5	.5	24	1.76	.269	5	6	.93	45	.002	6	.73	.025	.30	2	1	6.6	<1	3.34	2
0589	1.0	187	4	81	.1	53	44	1584	10.04	43	2	<2	2	37	.2	2.4	<.5	33	1.07	.232	6	9	1.20	49	.001	6	.70	.077	.16	1	<1	6.4	1	4.24	2
0590	3.2	166	4	79	.1	62	48	1721	13.49	36	1	<2	1	65	.2	1.2	<.5	34	2.24	.209	4	13	1.72	53	.001	1	.78	.072	.14	<1	<1	7.7	<1	5.09	1
0591	.9	144	2	78	.2	73	46	2232	12.01	15	2	<2	2	68	<.2	<.5	<.5	36	2.69	.196	5	11	2.21	128	.001	9	.73	.070	.15	1	<1	8.3	<1	2.62	2
0592	2.2	186	3	88	.1	85	52	1695	12.09	23	2	<2	2	95	<.2	<.5	<.5	26	3.91	.116	1	14	2.63	101	.001	4	.71	.041	.17	<1	<1	8.7	<1	2.96	1
STANDARD C3	26.8	72	37	179	5.7	38	12	885	3.36	60	24	<2	21	32	23.8	15.8	24.1	84	.65	.098	20	185	.67	165	.092	23	1.81	.045	.18	16	1	4.7	<1	.03	8
STANDARD G-2	1.5	2	3	47	<.1	8	4	577	2.04	<1	2	<2	4	78	<.2	<.5	<.5	42	.69	.104	8	82	.62	238	.136	2	.91	.085	.52	2	<1	2.7	<1	<.01	5

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 2 2000 DATE REPORT MAILED: Oct 13/00 SIGNED BY: ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002641R Page 1
305 - 455 Grenville St., Vancouver BC V6C 1T1

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0515	.9	59	7	50	<.1	49	21	1624	4.84	158	2	<2	5	53	.4	1.0	<.5	6	1.47	.066	10	9	1.04	96	.002	9	.41	.011	.22	1	<1	4.0	<1	.89	1
0516	.8	40	10	47	.1	55	16	2154	4.08	122	1	<2	2	227	.7	.7	<.5	14	6.52	.106	3	9	2.41	65	.009	7	.37	.011	.20	1	<1	6.1	<1	.47	1
0517	1.9	25	9	46	<.1	57	30	3073	5.29	138	1	<2	1	236	.3	.9	.5	19	8.32	.173	2	9	3.06	78	.021	7	.47	.014	.26	1	<1	8.9	<1	.99	2
0518	.9	12	68	67	1.6	138	55	4475	8.54	369	1	7	1	284	.5	1.3	4.9	19	11.22	.132	2	16	3.83	70	.020	9	.43	.012	.23	2	<1	11.7	1	2.73	2
0519	.8	2	33	30	1.5	40	11	1752	4.05	158	2	4	7	100	<.2	.9	3.0	7	2.98	.053	6	5	1.07	72	.002	8	.35	.008	.20	1	<1	5.0	1	2.16	1
0520	1.5	1	4	11	<.1	11	<1	1291	1.32	20	1	<2	11	68	<.2	<.5	<.5	3	2.27	.070	18	3	.81	58	.002	5	.28	.006	.17	<1	<1	3.3	<1	.12	1
0521	1.9	4	7	18	.1	76	11	2193	2.75	125	1	<2	6	126	<.2	<.5	<.5	13	4.54	.096	9	17	1.63	133	.009	9	.60	.017	.34	1	<1	5.9	<1	.42	2
0522	1.5	16	8	15	.1	112	9	2227	2.19	119	3	<2	3	90	<.2	<.5	<.5	15	3.75	.151	11	18	1.31	188	.015	8	.71	.020	.38	<1	<1	7.0	<1	.21	2
0523	1.1	28	23	13	.6	82	35	1129	8.13	335	3	5	3	61	<.2	2.2	11.3	11	2.25	.090	7	11	.81	110	.009	7	.65	.014	.32	2	6	3.9	1	6.72	2
0524	5.3	58	8	56	.1	96	29	728	5.61	104	2	<2	4	46	<.2	1.2	.8	10	1.15	.064	10	19	1.41	130	.006	5	.48	.013	.26	1	<1	3.4	<1	1.10	1
0525	.4	18	5	32	<.1	22	10	371	2.77	43	2	<2	7	11	<.2	.6	<.5	3	.12	.037	17	10	.68	126	.002	3	.41	.010	.22	3	<1	1.7	<1	.26	1
0526	3.9	88	8	91	.1	90	34	415	4.61	101	3	<2	2	48	<.2	1.6	<.5	11	.93	.119	8	22	1.04	168	.004	6	.47	.012	.25	1	<1	4.5	<1	1.60	1
0527	1.1	47	6	85	<.1	68	20	325	3.84	52	2	<2	3	49	<.2	1.1	<.5	7	1.00	.062	9	14	1.05	147	.004	7	.44	.011	.23	2	<1	3.0	<1	1.42	1
0528	4.7	24	7	31	.1	36	10	174	3.96	28	1	<2	3	23	<.2	2.8	<.5	5	.47	.029	9	18	.53	102	.001	3	.34	.009	.18	1	3	1.3	1	2.61	<1
0529	.6	33	4	56	<.1	39	14	299	3.65	16	2	<2	5	43	<.2	.5	<.5	4	.95	.034	10	12	.77	161	.002	5	.39	.010	.21	3	<1	2.1	<1	1.56	1
0530	2.8	47	6	68	.1	84	23	1094	5.63	33	1	<2	12	232	<.2	1.0	<.5	9	5.12	.074	5	15	2.34	177	.009	9	.48	.014	.25	1	<1	4.3	<1	1.29	2
RE 0530	2.9	46	7	69	.1	85	23	1099	5.67	32	1	<2	12	234	<.2	<.5	<.5	9	5.14	.075	5	16	2.36	181	.008	6	.48	.014	.25	<1	1	4.2	<1	1.31	2
0531	.6	97	9	139	.2	121	52	1237	8.53	89	1	<2	1	314	.3	5.1	.9	12	6.64	.096	2	20	3.01	161	.008	3	.50	.014	.25	2	17	5.4	3	3.70	2
0533	.7	105	6	89	.1	130	37	428	5.56	101	1	<2	1	43	<.2	2.7	<.5	18	.74	.161	6	25	.93	126	.007	5	.57	.015	.28	3	3	4.7	<1	2.73	1
0534	7.5	75	12	87	.2	72	28	274	13.81	94	1	<2	1	43	.3	6.3	<.5	15	.85	.206	5	18	.58	41	.006	3	.42	.008	.20	1	11	3.2	1	11.40	<1
0535	3.7	69	9	116	.2	71	27	216	7.68	61	2	<2	1	55	.2	3.0	<.5	13	1.03	.296	5	17	.71	77	.008	2	.53	.010	.26	1	2	3.4	1	6.35	1
0537	3.4	83	8	151	.2	66	31	161	7.13	53	1	<2	1	43	.3	2.5	<.5	20	.80	.311	6	13	.49	67	.010	3	.58	.012	.27	1	2	3.5	<1	5.72	1
0538	3.4	87	8	193	.2	55	39	201	6.61	92	1	<2	1	43	.5	3.4	<.5	18	.84	.259	7	10	.45	72	.008	6	.57	.017	.28	3	1	3.0	<1	5.32	1
0539	5.9	60	7	139	.1	60	36	146	4.55	92	2	<2	1	49	.2	1.8	<.5	18	.74	.280	8	16	.33	77	.009	7	.56	.011	.27	1	1	3.1	<1	3.59	1
0540	4.0	81	8	172	.1	55	42	259	6.21	66	1	<2	1	51	.3	1.8	<.5	17	.83	.303	7	12	.44	84	.010	5	.65	.014	.31	3	1	3.1	1	4.91	1
0541	14.0	105	8	122	.2	65	48	348	8.21	78	1	<2	1	55	.2	2.5	<.5	17	1.08	.266	6	12	.52	88	.013	5	.66	.016	.30	3	1	3.7	1	6.49	1
0542	5.4	119	20	50	1.2	78	53	962	11.74	408	1	6	2	168	<.2	<.5	4.7	19	2.31	.361	7	11	.83	92	.015	10	.69	.014	.33	1	1	8.2	<1	8.72	1
0543	1.3	16	23	64	.7	75	61	1166	8.70	297	1	5	2	117	<.2	<.5	2.7	24	1.79	.393	9	6	.89	104	.014	6	.79	.016	.34	2	1	7.8	1	4.73	2
0544	4.0	62	19	48	.3	91	69	531	9.22	303	1	<2	2	130	.2	1.8	4.6	24	1.97	.296	7	10	.54	87	.023	8	.71	.015	.35	1	4	6.8	2	8.65	1
0545	2.1	59	22	53	.5	86	67	1055	12.55	300	1	2	2	158	<.2	1.0	6.0	26	2.28	.262	6	6	.92	80	.021	7	.68	.014	.33	2	1	9.7	2	9.94	2
0546	4.1	56	49	50	1.5	91	75	1178	13.53	397	1	9	2	142	<.2	2.5	9.2	29	2.35	.262	7	9	1.03	68	.019	6	.63	.012	.30	1	2	8.6	2	11.00	2
0547	1.4	68	16	60	.4	81	67	1384	12.51	162	1	<2	2	152	.2	.9	4.4	25	2.77	.254	6	5	1.39	78	.008	5	.63	.015	.27	1	2	9.5	1	7.76	2
0548	3.8	56	20	34	.2	65	40	874	8.33	166	1	<2	1	96	.3	<.5	1.4	21	2.21	.189	6	12	.64	84	.017	7	.62	.012	.31	1	2	5.5	2	7.47	2
0549	1.4	89	12	46	.1	88	53	1591	9.97	279	1	<2	1	104	<.2	.8	1.5	22	2.46	.134	5	9	1.11	105	.015	4	.62	.014	.31	2	7	6.2	1	6.41	2
0550	3.3	48	22	29	.3	114	62	1027	7.60	312	1	2	1	80	<.2	2.0	3.4	21	1.73	.166	5	11	.62	73	.014	9	.61	.011	.30	2	9	5.9	1	6.47	2
STANDARD C3	27.9	68	35	172	5.4	36	12	812	3.40	59	24	2	21	29	22.3	18.6	23.4	81	.60	.093	21	173	.63	160	.089	20	1.85	.041	.17	15	1	4.6	<1	.03	7
STANDARD G-2	1.7	3	3	44	<.1	7	4	549	2.04	<1	3	<2	4	78	<.2	<.5	<.5	40	.68	.101	10	78	.61	244	.137	<1	1.03	.118	.51	2	<1	2.6	<1	<.01	4

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 2 2000 DATE REPORT MAILED: Oct 16/00 SIGNED BY: ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0601	1.8	39	6	84	.1	108	61	2272	9.45	213	1	<2	1	127	.3	<.5	3.1	21	2.57	.179	4	5	1.54	48	.001	8	.47	.014	.24	1	9	9.8	<1	4.35	1
0602	1.8	53	11	71	.2	104	61	1993	11.61	248	1	<2	1	91	<.2	4.1	5.0	20	2.06	.168	4	6	1.30	30	.001	10	.47	.012	.24	2	14	7.7	1	7.19	1
0603	3.3	70	9	62	.2	103	51	2217	11.73	255	1	<2	1	170	<.2	2.6	2.5	20	3.24	.161	3	7	1.76	64	.001	8	.44	.010	.23	<1	9	8.7	<1	6.58	1
0604	1.7	47	90	48	3.4	100	58	1779	14.09	357	1	36	1	129	<.2	<.5	4.6	24	2.73	.215	5	7	1.50	49	.001	11	.52	.012	.28	2	3	9.8	<1	9.07	1
0605	3.2	40	79	49	3.1	96	58	1814	13.43	346	1	34	1	153	<.2	<.5	4.0	23	3.21	.236	5	9	1.55	67	.001	13	.50	.011	.27	1	2	10.2	<1	8.62	2
0606	1.3	13	13	47	.5	64	51	1909	9.71	206	1	4	1	207	.2	<.5	1.4	26	4.70	.241	4	4	2.00	100	.001	5	.53	.018	.26	<1	<1	12.8	<1	2.91	2
0607	4.5	64	105	38	2.8	143	89	1264	17.66	446	1	16	1	201	<.2	<.5	11.6	32	3.49	.229	4	10	1.36	36	.002	11	.46	.010	.22	1	3	11.8	<1	13.08	1
0608	1.5	46	53	37	1.1	98	75	1338	12.85	422	1	5	1	181	<.2	<.5	5.0	25	3.45	.236	5	6	1.30	44	.001	7	.52	.013	.28	2	2	10.9	<1	10.50	1
RE 0608	1.8	47	54	37	1.1	99	76	1351	13.01	426	1	6	1	189	<.2	.5	5.3	25	3.53	.238	4	6	1.31	45	.001	12	.51	.013	.27	1	2	10.9	<1	10.80	2
0609	2.5	39	14	28	.2	62	45	2062	6.03	277	1	<2	1	379	<.2	.9	1.1	22	6.18	.290	3	4	1.94	132	.002	8	.53	.017	.28	1	<1	11.7	<1	3.12	2
0610	2.6	80	89	37	1.4	64	63	998	17.94	609	1	6	2	148	<.2	1.7	9.1	23	2.41	.218	4	8	.96	43	.002	8	.48	.012	.25	3	1	7.5	1	14.29	1
0611	2.9	69	39	31	.9	87	80	1598	12.62	600	1	6	1	167	<.2	.5	4.2	24	3.09	.258	4	8	1.36	54	.002	4	.50	.014	.25	1	1	9.0	<1	9.11	2
0612	2.3	147	4	63	.1	66	51	1717	8.22	158	1	<2	1	74	.2	<.5	<.5	21	1.74	.226	7	8	1.20	97	.001	4	.52	.023	.21	1	1	7.0	<1	2.42	2
STANDARD C3	27.1	69	35	171	5.5	36	11	805	3.38	59	24	3	21	30	22.6	16.4	23.7	84	.61	.094	19	175	.62	160	.088	23	1.85	.040	.17	15	1	4.7	<1	.03	7
STANDARD G-2	1.5	2	3	49	<.1	7	4	556	2.04	<1	2	<2	4	73	.5	<.5	<.5	43	.67	.103	10	78	.62	234	.130	3	.95	.079	.48	2	<1	2.7	<1	.01	4

Sample type: CORE PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ____

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002438R

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0459	6.5	47	9	86	<.1	63	13	473	3.24	172	3	<2	4	67	1.3	1.6	<.5	24	.93	.179	9	17	.24	110	.001	6	.54	.010	.18	3	<1	3.7	<1	.50	1
0460	5.3	116	12	206	<.1	121	22	565	6.10	374	6	<2	5	45	1.0	4.1	<.5	32	.63	.149	13	29	.14	88	.001	2	1.06	.010	.19	12	<1	6.0	<1	.07	1
0461	1.1	51	21	70	.2	76	28	2576	3.45	120	2	<2	5	124	2.1	<.5	<.5	12	3.97	.110	8	9	1.50	62	.001	2	.57	.010	.21	1	<1	5.8	<1	.35	<1
0462	3.8	70	5	103	.3	62	19	3251	7.43	107	1	<2	1	199	1.7	<.5	<.5	23	8.30	.083	3	21	3.72	50	.002	5	.67	.010	.15	4	1	6.2	1	.83	1
0463	3.5	39	11	48	.6	56	25	3211	8.10	188	<1	3	1	175	1.6	.7	1.9	14	7.34	.084	2	18	2.89	50	.002	<1	.52	.008	.18	4	<1	6.3	<1	2.32	1
0464	2.9	72	12	95	.5	77	40	3120	8.90	177	1	<2	1	163	1.8	.5	4.0	20	6.34	.173	2	13	2.57	68	.003	1	.76	.008	.19	3	<1	7.2	<1	2.61	<1
0465	2.6	36	18	52	.6	110	53	4756	16.16	350	<1	<2	1	164	.6	<.5	4.0	15	10.43	.151	2	11	4.52	83	.003	4	.77	.009	.23	2	2	7.9	<1	5.29	<1
0466	2.5	6	26	42	.9	109	32	1525	9.77	469	2	<2	6	59	.2	<.5	7.2	8	2.58	.057	3	7	.98	52	.001	3	.41	.009	.16	2	<1	3.3	<1	6.64	1
0467	1.5	1	2	14	.2	38	7	1659	1.97	92	4	<2	8	76	.4	<.5	<.5	5	2.85	.071	7	3	1.23	81	.001	3	.37	.010	.22	<1	<1	3.5	<1	.57	1
0468	3.0	59	13	65	.3	87	39	362	11.58	255	<1	<2	1	71	.3	4.6	6.4	14	1.61	.268	2	9	.47	25	.002	6	.55	.009	.22	10	14	3.2	4	10.33	1
0469	3.3	128	7	89	.1	164	53	672	5.38	147	2	<2	1	18	1.0	.8	<.5	12	.40	.092	3	20	.94	77	.001	7	.45	.010	.24	2	<1	4.2	<1	2.44	<1
0470	2.0	111	3	38	.3	196	53	2181	8.27	274	<1	<2	<1	93	<.2	<.5	1.8	15	2.98	.126	1	17	1.94	89	.001	6	.51	.009	.23	1	<1	8.4	<1	2.56	1
RE 0470	2.0	110	3	37	.3	192	59	2163	8.21	275	<1	<2	1	94	<.2	<.5	1.2	14	2.97	.128	1	17	1.93	90	.001	5	.51	.009	.23	1	<1	8.3	<1	2.53	1
0471	3.2	13	12	41	.7	148	73	2659	13.71	458	<1	<2	1	117	<.2	1.5	20.2	21	5.42	.324	2	12	1.92	51	.002	8	.91	.010	.29	2	3	7.7	<1	8.41	1
0472	2.5	120	11	147	.1	62	50	574	6.11	136	1	<2	1	47	1.1	1.1	1.3	14	1.10	.283	4	7	.55	60	.002	5	.54	.011	.25	2	1	3.0	<1	4.27	1
0473	6.9	100	9	137	.1	49	33	505	5.64	76	1	<2	1	45	.7	1.0	<.5	15	.96	.302	4	9	.60	56	.002	10	.61	.013	.27	2	<1	3.1	<1	3.46	1
0475	8.1	73	2	154	.2	63	58	929	5.47	108	1	<2	1	81	.8	<.5	<.5	16	1.26	.357	5	6	.72	147	.002	7	.55	.013	.27	1	<1	4.7	<1	1.64	1
0477	6.2	37	8	79	.2	65	56	665	6.77	116	<1	<2	2	103	.7	.7	2.8	12	1.94	.458	5	8	.55	65	.001	7	.73	.016	.30	4	1	4.5	<1	4.27	2
0478	6.0	50	13	64	.4	85	77	984	11.76	122	<1	<2	2	126	.7	.6	5.2	23	2.88	.483	4	7	.84	40	.002	6	1.00	.018	.35	2	3	6.8	2	7.08	2
0479	1.9	110	11	91	.3	96	73	1009	9.55	94	<1	<2	2	55	.6	1.1	3.7	17	1.25	.275	3	6	.71	31	.001	8	.67	.015	.25	1	4	6.1	2	6.85	2
0480	3.3	177	5	139	.1	65	45	753	5.64	79	<1	<2	1	42	1.0	1.4	<.5	16	.94	.191	5	13	.48	32	.001	9	.59	.015	.25	3	1	4.8	<1	3.28	1
0481	2.6	131	25	93	.4	66	48	345	10.55	85	<1	<2	2	47	.7	2.0	.7	17	1.37	.208	3	10	.30	32	.002	11	.58	.013	.24	2	5	3.2	4	10.25	1
0482	2.7	84	8	59	.3	116	58	2069	12.23	204	<1	<2	1	114	.9	1.5	1.0	19	2.31	.154	2	14	1.68	65	.001	5	.76	.015	.27	1	1	8.0	1	4.76	<1
0483	.7	68	6	62	.3	99	70	3229	13.51	182	<1	<2	1	124	.8	.6	.8	22	3.20	.191	2	5	2.43	89	.001	10	.80	.014	.28	1	2	10.2	3	2.98	1
0484	1.8	28	8	45	.3	162	80	2643	13.31	390	1	<2	2	145	<.2	<.5	2.3	21	4.01	.160	2	15	2.36	81	.002	6	.84	.018	.31	1	3	10.9	<1	4.51	1
0485	1.5	26	26	29	1.0	163	103	1742	14.41	537	1	3	2	170	<.2	1.0	6.6	23	4.44	.304	3	7	1.47	46	.003	7	1.00	.014	.34	2	3	9.3	<1	9.30	1
0486	4.3	41	14	54	.1	62	21	260	4.95	117	1	<2	6	37	.6	1.0	2.0	4	.72	.067	7	16	.33	64	.001	11	.44	.010	.23	1	2	1.4	<1	4.64	1
0487	1.5	60	9	188	.3	90	33	162	4.36	129	1	<2	4	41	1.2	1.2	<.5	7	.56	.062	6	17	.21	55	.001	4	.43	.010	.23	3	3	1.7	<1	4.12	<1
0488	5.1	27	11	51	<.1	39	13	93	3.09	67	1	<2	7	17	.4	.9	.5	2	.20	.037	11	19	.10	84	.001	4	.33	.009	.20	1	2	.8	2	2.92	<1
0489	3.9	18	9	40	<.1	42	15	92	2.74	59	2	<2	7	17	.3	.8	1.1	2	.22	.038	12	16	.08	98	<.001	6	.35	.010	.22	1	1	1.1	1	2.69	1
0490	.7	13	9	19	<.1	34	14	66	2.66	114	1	<2	6	14	.4	<.5	2.8	2	.19	.041	11	12	.05	89	<.001	8	.35	.011	.22	4	<1	.7	1	2.67	<1
0491	5.6	6	8	13	.5	68	38	131	11.99	1197	<1	<2	5	46	<.2	<.5	7.0	5	.76	.140	4	17	.14	40	.001	4	.50	.010	.21	1	<1	1.3	<1	11.88	1
0492	.4	48	9	28	<.1	23	9	67	2.58	94	1	<2	6	12	.4	.6	1.4	2	.17	.030	10	11	.06	76	<.001	5	.28	.009	.18	4	<1	.5	<1	2.52	<1
STANDARD C3	26.4	71	35	174	5.3	37	12	801	3.15	56	23	<2	20	29	24.5	15.0	21.9	79	.60	.094	18	172	.63	157	.086	25	1.77	.042	.17	13	1	4.3	<1	.03	8
STANDARD G-2	1.3	2	2	39	<.1	7	3	473	1.74	<1	2	<2	3	66	<.2	<.5	<.5	36	.59	.092	6	68	.55	209	.113	3	.81	.079	.45	2	<1	2.2	<1	<.01	4

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CU, PB, SB, BI, TH, U & B = 2,000 PPM; CO, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 2 2000 DATE REPORT MAILED: Oct 13/00 SIGNED BY: D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002215R Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0391	2.5	196	27	178	.5	84	50	1828	10.65	298	2	2	1	171	2.1	1.1	1.8	24	3.71	.189	2	10	2.22	67	.002	10	1.26	.013	.27	3	<1	7.6	<1	4.34	3
0392	3.5	165	35	154	.6	126	55	2000	11.91	346	2	2	1	188	2.3	.8	3.6	18	4.36	.169	2	11	2.59	76	.002	5	1.17	.014	.22	3	<1	7.6	<1	5.76	3
0393	4.1	217	28	226	.6	144	59	1696	11.28	342	2	3	1	136	1.4	.9	2.6	19	2.41	.166	2	14	1.59	53	.002	4	1.18	.013	.29	4	<1	6.4	<1	6.43	2
0394	1.2	20	5	30	<.1	43	18	419	2.35	170	1	<2	4	42	.8	<.5	<.5	6	.72	.028	6	9	.32	88	<.001	5	.31	.012	.20	3	<1	1.8	<1	1.52	1
0395	7.5	20	30	35	1.0	148	88	1048	10.05	703	<1	8	2	84	.7	.5	8.1	10	1.84	.211	2	8	.81	50	.001	2	.52	.007	.16	2	<1	4.4	<1	9.52	2
0396	.5	28	7	38	.2	53	36	2146	4.86	189	2	<2	1	222	1.2	<.5	<.5	22	4.36	.203	3	6	1.61	133	.002	4	.62	.015	.27	1	24	9.4	1	1.20	1
0397	.6	48	2	101	.2	131	60	1992	9.64	255	1	<2	1	65	<.2	<.5	<.5	23	1.48	.137	6	6	2.04	151	.003	3	.77	.016	.29	1	1	7.2	1	.31	2
0398	.7	136	6	100	.2	71	49	1761	8.53	109	1	<2	<1	62	.6	<.5	<.5	19	1.77	.131	5	5	1.84	132	.002	6	.59	.025	.20	<1	<1	6.0	<1	.29	2
0399	1.0	77	<2	93	<.1	61	38	1738	8.21	62	1	<2	1	34	.3	<.5	<.5	21	.87	.138	6	5	1.28	153	.003	5	.53	.035	.21	<1	<1	5.8	1	.26	3
0400	1.2	143	6	93	.3	87	55	1070	7.87	135	1	<2	1	58	.7	.9	<.5	19	1.43	.137	2	8	1.31	65	.001	7	.79	.021	.28	1	1	4.1	3	4.61	2
0401	1.3	119	6	106	.3	80	53	711	9.24	172	<1	<2	<1	89	1.0	.9	.5	16	1.41	.129	2	10	.90	32	.002	4	.77	.019	.27	2	2	3.9	4	8.16	2
0402	3.6	114	11	266	.1	53	37	271	13.54	115	1	<2	1	33	1.0	3.5	<.5	16	.78	.122	1	14	.52	24	.002	7	.97	.024	.26	2	5	2.5	6	13.82	3
0403	1.1	123	5	154	.1	115	54	900	8.65	147	<1	<2	1	66	.6	1.3	<.5	12	1.77	.087	1	14	1.65	60	.001	5	.59	.020	.20	1	2	5.0	2	4.95	2
0404	3.5	92	8	599	.1	63	46	429	12.03	166	1	<2	1	55	2.3	7.2	.5	18	1.43	.159	2	15	.87	38	.002	8	.94	.033	.24	3	3	3.8	7	11.45	3
0405	1.6	206	8	174	.1	139	67	623	8.17	233	<1	<2	1	41	.2	3.0	<.5	15	.90	.134	2	17	.83	41	.001	6	.72	.025	.23	2	3	3.8	5	6.14	2
0406	2.3	177	5	86	.1	95	52	787	6.61	143	<1	<2	2	39	.6	1.9	<.5	22	.80	.172	4	12	.74	53	.002	5	.75	.043	.28	2	2	4.3	1	3.92	2
0408	2.0	180	6	103	.1	123	63	936	7.69	176	<1	<2	<1	53	.7	1.3	<.5	15	1.45	.135	2	12	1.24	58	.001	3	.77	.028	.23	2	1	4.3	2	4.58	2
0409	2.3	159	7	58	.1	129	69	648	7.06	298	<1	<2	1	51	<.2	.9	1.2	17	1.27	.161	2	14	.71	49	.001	6	.80	.022	.28	2	2	4.3	1	5.72	2
0410	7.8	167	8	81	.1	80	50	1046	6.18	157	<1	<2	1	40	.7	<.5	.6	19	.98	.201	4	10	.82	97	.001	6	.64	.023	.27	2	<1	4.8	<1	2.69	2
RE 0410	8.3	163	8	79	.1	79	51	1045	6.20	155	<1	<2	1	40	.6	.7	<.5	18	.98	.200	4	10	.82	101	.001	6	.63	.023	.27	2	1	4.7	1	2.69	2
0411	4.6	145	2	75	.1	55	37	1332	6.43	94	<1	<2	1	35	.4	<.5	<.5	20	.66	.169	6	13	.82	146	.001	9	.58	.025	.23	3	<1	5.9	<1	1.08	2
0412	1.3	274	3	89	.5	94	58	2058	9.21	241	<1	<2	1	48	<.2	.8	<.5	21	.72	.177	4	6	1.57	97	.001	5	.84	.038	.23	1	<1	7.8	<1	2.82	2
0413	1.2	57	26	42	1.5	128	87	1424	14.12	683	1	4	1	256	<.2	1.8	2.9	23	2.56	.197	2	6	2.28	53	.002	8	1.05	.021	.26	1	3	10.8	3	11.84	3
0414	1.3	36	15	38	.7	100	87	1268	10.58	444	<1	<2	1	254	<.2	.9	2.2	28	2.79	.264	3	5	1.99	62	.003	6	1.24	.023	.35	1	1	10.7	<1	6.95	3
0415	1.1	29	15	44	1.1	204	91	1144	11.15	474	<1	3	2	146	<.2	1.3	2.4	17	1.69	.161	2	16	1.73	50	.001	7	.93	.026	.28	1	1	8.9	3	7.87	2
0416	1.0	29	9	67	.5	106	62	2238	12.41	295	<1	<2	1	106	<.2	.7	1.1	28	1.07	.270	4	7	2.48	70	.004	6	1.34	.038	.36	1	1	9.2	2	4.28	2
0417	.4	10	2	70	.2	144	65	2252	9.61	296	<1	<2	1	133	<.2	<.5	.9	20	2.14	.149	2	15	2.71	159	.001	6	.84	.023	.28	<1	<1	9.7	2	1.70	2
0418	1.3	7	3	74	.1	68	48	2199	8.90	170	<1	<2	1	80	.7	<.5	1.0	22	1.12	.267	6	6	1.84	128	.002	7	.88	.027	.33	1	<1	7.5	2	1.67	2
0419	1.7	20	8	89	.3	96	80	2067	14.33	243	<1	2	1	138	2.5	1.8	1.7	26	2.15	.246	3	9	3.14	62	.002	5	1.39	.036	.32	1	1	9.9	2	5.52	3
0420	1.7	26	12	63	.4	103	84	1613	14.72	235	1	<2	1	177	.8	1.4	3.2	27	2.79	.280	3	8	3.11	60	.002	6	1.27	.029	.29	1	2	11.3	2	7.56	3
0421	1.5	22	12	53	.4	88	76	1372	11.89	219	<1	<2	1	110	.7	.7	3.0	30	1.64	.254	4	8	1.94	43	.002	7	1.26	.034	.32	1	1	10.0	<1	6.36	2
0422	.9	8	3	44	.2	36	44	1497	7.04	128	<1	<2	1	164	.5	<.5	.6	29	2.15	.389	5	3	1.61	106	.002	9	.87	.023	.34	1	<1	8.6	<1	2.20	3
0423	3.1	16	18	24	.9	89	67	663	8.54	314	<1	6	1	203	<.2	<.5	3.1	27	2.87	.373	4	5	1.25	45	.002	7	1.02	.020	.32	1	2	9.2	<1	6.43	3
0424	.8	9	5	17	.3	60	55	1055	7.23	210	<1	<2	1	288	.7	.5	1.7	20	4.30	.380	4	3	1.88	97	.002	7	.95	.017	.32	1	1	10.0	<1	3.64	2
0425	1.0	38	<2	79	.1	69	64	1944	9.39	148	<1	<2	1	130	.5	<.5	<.5	26	2.23	.252	5	5	2.79	215	.002	4	.88	.020	.29	<1	<1	9.3	<1	1.15	2
STANDARD C3	27.4	68	36	177	5.5	37	13	851	3.50	59	25	<2	22	30	23.3	15.6	24.1	82	.61	.095	19	180	.64	160	.092	24	1.90	.043	.18	14	1	4.6	<1	.03	8
STANDARD G-2	1.6	3	2	45	<.1	7	4	559	2.01	<1	2	<2	4	71	<.2	<.5	<.5	41	.66	.101	7	79	.61	230	.127	1	.92	.081	.50	2	<1	2.5	<1	<.01	6

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 6 2000 DATE REPORT MAILED: Oct 16/00 SIGNED BY: ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0426	.6	36	3	62	.2	57	52	1464	8.65	117	1	<2	1	201	.5	<.5	1.1	32	3.82	.300	3	4	2.05	225	.002	4	.57	.023	.31	<1	<1	10.0	<1	1.37	2
0427	.8	10	2	62	.2	51	48	1625	9.25	84	<1	<2	1	196	.4	.5	<.5	35	3.59	.317	4	3	2.24	253	.002	3	.58	.022	.31	<1	<1	10.7	<1	1.05	3
0428	1.0	9	2	60	.2	49	55	1601	8.45	77	<1	<2	1	123	.3	<.5	1.1	33	2.12	.296	5	3	1.77	246	.002	2	.60	.028	.31	<1	1	9.9	<1	1.09	2
0429	.9	10	<2	94	.2	81	80	2563	12.59	118	<1	<2	1	180	.5	<.5	<.5	36	3.46	.270	4	6	2.59	240	.003	2	.57	.026	.31	<1	1	11.9	1	.75	2
0430	.6	11	<2	64	.1	75	70	1890	9.85	103	<1	<2	2	104	.3	<.5	<.5	29	1.70	.372	8	5	1.82	248	.002	<1	.67	.031	.34	<1	<1	9.2	1	.62	2
0431	1.1	69	4	105	.4	54	50	1870	9.34	96	<1	3	1	71	.3	<.5	.9	26	1.09	.327	5	6	1.36	124	.002	6	.60	.038	.30	<1	<1	7.9	1	1.87	2
0432	2.0	37	4	58	.3	61	50	1722	9.85	108	<1	<2	<1	93	.4	<.5	1.0	29	1.59	.293	4	10	1.57	116	.001	4	.60	.042	.29	<1	2	9.6	1	2.68	3
0433	.8	128	3	68	.2	50	46	1636	7.70	54	<1	<2	<1	59	.2	<.5	<.5	23	1.22	.284	7	7	1.13	187	.002	1	.54	.055	.24	1	1	6.2	1	1.40	2
0434	1.6	112	2	85	.1	57	51	1609	6.62	27	1	<2	1	59	.2	<.5	<.5	26	1.69	.241	9	8	1.27	170	.001	6	.54	.052	.21	<1	<1	7.1	<1	.52	2
0435	.3	158	2	98	.1	59	54	1542	7.06	7	<1	<2	1	37	<.2	<.5	<.5	23	.88	.257	9	6	1.01	164	.001	3	.55	.077	.19	<1	<1	6.7	<1	.83	2
0436	2.3	145	5	78	.2	76	61	1001	7.51	9	<1	<2	1	38	<.2	1.0	<.5	26	.99	.236	5	10	.66	50	.001	6	.54	.071	.19	<1	1	5.6	1	3.93	2
0437	.8	224	4	88	.3	70	58	1380	8.28	10	<1	<2	1	44	<.2	1.0	<.5	24	1.28	.206	4	8	.96	81	.001	2	.54	.069	.18	1	1	6.2	3	3.03	3
0438	1.7	168	2	111	.2	82	55	1473	7.69	6	<1	<2	1	54	<.2	<.5	<.5	29	1.11	.156	5	9	1.19	198	.001	3	.63	.058	.17	<1	<1	9.3	1	.89	2
RE 0438	1.7	163	2	111	.2	80	55	1448	7.45	6	<1	<2	1	53	<.2	<.5	<.5	28	1.10	.153	5	9	1.17	200	.001	1	.62	.058	.16	<1	<1	9.1	<1	.89	2
0439	.2	114	<2	105	.2	84	47	1692	7.98	2	<1	<2	<1	47	<.2	<.5	<.5	28	1.31	.155	8	9	1.39	302	.001	4	.60	.063	.17	<1	<1	9.1	<1	.17	2
0440	1.4	103	<2	92	.2	70	38	1451	7.13	9	<1	<2	<1	52	<.2	<.5	<.5	18	1.52	.145	5	13	1.32	134	<.001	1	.61	.082	.17	<1	<1	6.7	<1	.31	1
0441	.4	156	<2	96	.2	82	43	1425	7.62	26	<1	<2	<1	76	<.2	<.5	<.5	21	2.69	.120	2	14	1.64	145	.001	1	.53	.064	.18	<1	<1	7.3	2	1.02	1
0442	1.3	131	<2	87	.1	104	41	1350	7.76	9	<1	<2	1	60	<.2	<.5	<.5	18	1.94	.124	2	20	1.45	155	.001	<1	.52	.060	.18	<1	<1	6.7	2	1.25	2
0443	1.5	95	2	101	.1	104	51	1902	9.64	54	<1	<2	<1	63	.3	<.5	<.5	19	2.16	.115	2	16	1.80	136	.001	<1	.49	.061	.18	<1	<1	8.0	<1	1.58	1
0444	.4	113	<2	82	.3	98	48	1579	7.19	12	1	<2	<1	113	<.2	1.0	<.5	37	5.32	.107	2	27	2.31	162	<.001	1	.67	.037	.17	1	<1	10.0	1	.96	2
STANDARD C3	27.5	67	36	167	5.4	38	12	817	3.44	58	24	<2	19	30	25.6	15.6	23.2	83	.63	.102	19	183	.64	168	.093	23	1.87	.044	.18	15	1	4.6	<1	.04	8
STANDARD G-2	1.6	2	2	43	<.1	7	4	529	2.03	1	2	<2	3	72	<.2	<.5	<.5	41	.66	.105	8	76	.60	231	.132	5	.92	.081	.50	2	<1	2.5	<1	<.01	5

Sample type: CORE PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ____

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003727R

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
1540	.8	109	7	65	<.1	102	33	1918	6.50	77	1	<2	1	233	<.2	37.3	<.5	15	7.94	.110	2	15	3.69	53	.002	7	.31	.011	.17	2	<1	8.0	<1	.68	1
1541	1.6	43	13	41	.1	121	35	2432	5.88	187	1	<2	1	214	<.2	4.0	.8	14	7.92	.098	2	20	3.47	46	.002	9	.25	.008	.16	1	<1	6.7	<1	.70	1
1542	2.2	19	18	41	.1	54	30	2607	6.59	121	1	<2	1	275	.2	<.5	1.7	15	8.65	.118	2	13	3.29	69	.003	9	.29	.011	.17	2	<1	7.6	<1	1.43	1
1543	1.8	37	8	57	<.1	35	16	917	4.05	39	1	<2	2	149	<.2	1.1	<.5	7	5.57	.060	2	9	2.06	69	.001	6	.25	.009	.14	<1	<1	4.4	<1	.86	1
1544	2.8	57	17	42	.3	91	35	1384	7.27	168	1	<2	2	155	<.2	10.2	4.0	14	6.92	.124	1	12	2.47	74	.001	5	.32	.010	.18	8	<1	6.8	<1	3.01	1
1545	4.4	16	33	48	.3	96	33	2535	7.36	187	1	<2	1	219	.3	1.5	3.6	15	8.92	.093	2	16	3.26	63	.002	8	.25	.008	.14	3	<1	7.4	<1	1.82	1
1546	1.2	90	7	49	<.1	238	46	1229	5.70	33	1	<2	<1	249	<.2	<.5	.5	9	11.31	.074	1	24	3.65	99	.001	7	.28	.013	.12	1	<1	9.0	<1	.65	1
1547	3.5	82	9	53	.1	201	44	1057	5.82	22	1	<2	1	234	<.2	1.1	<.5	13	12.23	.079	1	22	3.32	132	.001	4	.35	.017	.12	<1	<1	8.6	<1	1.22	1
1548	3.5	93	10	105	<.1	108	38	1170	6.23	33	<1	<2	1	189	<.2	15.3	<.5	13	9.00	.153	2	12	3.03	127	.002	5	.37	.012	.13	1	<1	8.5	<1	1.08	2
1549	4.7	75	258	63	1.1	153	40	1722	6.87	225	1	<2	1	237	.3	2.6	3.2	13	10.92	.087	1	19	3.25	149	.002	6	.32	.015	.17	<1	<1	7.9	<1	1.23	1
1550	3.3	97	17	66	.1	146	41	1099	6.08	167	1	<2	1	238	.2	<.5	.7	11	8.51	.067	1	18	3.20	139	.002	7	.30	.010	.16	1	<1	7.8	<1	1.11	1
1551	2.7	57	64	60	.6	75	25	1926	6.69	137	1	<2	1	230	.2	.8	2.0	13	7.91	.093	1	15	2.60	123	.002	8	.29	.009	.17	1	<1	6.5	<1	1.37	1
1552	5.4	124	18	77	.1	53	41	1296	8.26	62	1	<2	1	175	<.2	1.0	.6	16	6.66	.169	1	6	1.84	107	.002	10	.37	.008	.20	2	<1	6.8	<1	3.38	1
1553	5.8	81	13	55	.1	60	40	1508	7.74	75	1	<2	1	212	.2	1.0	1.3	14	6.56	.129	1	7	1.81	106	.003	8	.34	.007	.19	1	<1	6.5	<1	2.89	1
1554	4.8	139	17	59	.1	56	43	1378	7.97	63	1	<2	1	237	<.2	1.7	.6	17	6.89	.157	1	5	1.95	112	.003	9	.38	.007	.18	1	<1	7.0	<1	2.96	2
1555	4.7	102	15	41	.1	78	31	1075	6.53	114	1	<2	2	146	<.2	2.4	<.5	15	3.80	.091	4	15	1.55	84	.001	1	.33	.009	.16	1	<1	5.6	<1	2.42	1
1556	2.1	57	5	41	.1	63	22	408	3.51	39	2	<2	5	39	<.2	1.2	<.5	9	.81	.069	13	17	.79	97	.001	4	.36	.008	.14	3	<1	3.7	<1	.98	1
1557	2.5	176	8	81	.1	45	40	1925	13.04	30	1	<2	1	98	<.2	<.5	<.5	20	3.40	.137	4	6	1.87	21	.001	<1	.62	.022	.08	<1	1	7.6	2	5.59	2
1558	.9	99	2	112	<.1	42	34	2087	8.91	6	1	<2	2	81	<.2	<.5	<.5	23	2.21	.163	7	5	1.82	134	.001	5	.48	.037	.10	1	<1	8.6	<1	.67	2
1559	2.1	144	10	67	.1	73	56	1032	11.70	46	1	<2	1	102	<.2	1.0	<.5	26	3.00	.134	4	9	1.35	53	.001	4	.42	.039	.10	<1	4	6.3	3	6.99	1
1560	.9	110	4	78	<.1	70	42	1345	10.09	29	1	<2	1	90	<.2	.9	<.5	25	2.47	.131	5	11	1.62	89	.001	2	.45	.038	.11	1	2	6.3	1	3.58	2
RE 1560	1.3	110	5	81	<.1	70	42	1327	10.05	29	1	<2	<1	89	<.2	<.5	<.5	22	2.44	.131	5	11	1.61	90	.001	<1	.44	.037	.11	2	2	6.2	<1	3.53	1
1561	1.7	117	4	67	.1	60	35	1568	9.04	27	1	<2	1	175	<.2	1.4	<.5	19	4.80	.120	2	10	2.40	128	.001	4	.50	.024	.11	<1	4	6.5	<1	2.44	2
1562	.7	98	3	73	<.1	109	35	1019	6.23	82	1	<2	1	95	<.2	<.5	<.5	15	2.56	.123	5	18	1.77	141	.001	5	.50	.030	.16	2	<1	6.5	<1	.74	1
1563	2.9	146	11	67	.2	118	52	1110	14.57	224	1	<2	1	87	<.2	3.3	.5	12	2.30	.096	4	14	1.39	47	.001	3	.37	.016	.15	1	11	4.4	2	11.07	1
1565	2.5	136	9	42	.2	71	51	1375	9.04	212	1	<2	1	148	.2	<.5	.9	18	3.79	.177	4	7	1.77	84	.002	<1	.45	.017	.20	<1	2	5.7	<1	4.95	2
1566	2.3	15	12	7	.1	73	60	417	10.79	743	3	<2	10	69	<.2	.6	2.9	3	1.32	.067	5	9	.47	42	.001	5	.35	.008	.18	3	<1	2.6	<1	11.12	1
1567	1.0	141	5	47	.1	190	63	2266	7.15	351	1	<2	1	185	<.2	<.5	.5	16	4.45	.099	3	16	2.49	147	.001	7	.35	.009	.19	1	<1	10.9	<1	1.64	1
1568	2.0	21	11	27	<.1	138	69	1068	5.86	378	2	<2	3	122	<.2	<.5	2.8	9	2.41	.112	5	16	1.09	80	.001	3	.39	.009	.21	2	1	6.0	<1	4.59	1
1569	2.3	38	5	80	<.1	45	16	228	3.92	85	3	<2	5	13	<.2	<.5	<.5	4	.25	.043	8	11	.50	104	.001	2	.30	.008	.17	1	<1	1.4	<1	2.34	1
STANDARD C3	27.3	67	35	165	5.6	36	12	820	3.38	57	24	3	23	29	22.8	17.1	23.6	80	.62	.096	19	175	.65	161	.091	23	1.88	.040	.17	15	1	4.7	<1	.03	7
STANDARD G-2	1.5	2	2	42	<.1	7	4	550	2.01	<1	3	<2	4	70	<.2	<.5	<.5	39	.67	.103	9	76	.63	238	.136	<1	.94	.084	.49	2	<1	2.6	<1	<.01	4

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 6 2000 DATE REPORT MAILED: Oct 14/00 SIGNED BY. C. Leong .D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003624R

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
1505	7.3	47	38	136	2.3	54	13	755	3.23	122	2	<2	4	155	.9	13.8	6.3	23	3.95	.105	8	14	1.49	116	<.001	8	.33	.014	.17	3	<1	3.7	<1	.76	<1
1506	7.1	33	65	179	.5	48	8	621	3.06	108	1	<2	3	141	1.6	9.1	1.3	44	4.07	.076	8	22	1.64	226	<.001	8	.34	.020	.15	4	<1	5.0	<1	.49	1
1507	1.1	65	8	122	.4	48	26	1473	5.05	88	1	<2	7	36	<.2	2.1	1.2	6	1.17	.051	21	13	.94	148	<.001	9	.37	.015	.21	3	<1	4.0	<1	.17	1
1508	1.1	59	5	80	.1	87	32	1716	6.17	134	1	<2	4	138	<.2	8.9	<.5	12	4.43	.071	8	18	2.43	113	.001	8	.37	.014	.22	1	<1	6.8	<1	.37	1
1509	1.4	66	21	66	.3	95	44	1826	6.61	191	1	<2	1	212	.2	4.0	1.9	14	7.17	.115	2	12	3.04	103	.001	8	.30	.010	.17	3	<1	8.0	<1	1.49	1
1510	1.6	51	8	42	.1	35	24	1177	4.38	35	<1	<2	2	181	<.2	4.4	.5	12	6.25	.093	3	12	2.23	82	.001	9	.31	.011	.16	2	<1	6.0	<1	.73	1
1511	1.8	31	11	50	.2	50	25	1193	4.85	72	1	<2	1	172	<.2	3.4	1.2	13	6.41	.107	2	11	2.34	97	.001	9	.31	.008	.15	2	<1	6.0	<1	1.29	1
1512	2.3	80	11	54	.1	121	32	1377	5.86	115	<1	<2	1	194	<.2	27.0	.8	13	7.77	.111	3	19	2.61	99	.001	7	.37	.009	.17	2	<1	8.2	<1	1.26	1
1513	1.7	56	7	66	.1	186	39	1253	5.69	58	<1	<2	1	274	<.2	46.4	<.5	11	11.79	.074	2	23	3.83	86	<.001	5	.33	.011	.13	<1	<1	10.5	<1	.39	1
1514	2.1	56	10	49	.1	203	42	1417	5.88	195	<1	<2	<1	253	<.2	12.6	1.7	11	8.85	.072	2	29	3.29	90	<.001	3	.30	.010	.15	2	<1	8.2	<1	1.12	1
1515	3.7	75	16	53	.1	185	47	1191	6.23	101	<1	<2	<1	240	<.2	2.5	1.1	11	9.40	.052	1	24	3.59	131	<.001	4	.31	.009	.14	1	<1	8.8	<1	1.18	1
1516	2.5	98	7	69	.1	146	42	1035	6.17	28	<1	<2	1	255	<.2	.5	<.5	11	11.26	.062	1	16	3.42	157	<.001	7	.33	.012	.14	1	<1	9.1	<1	1.12	1
1517	3.2	87	8	67	<.1	102	35	1002	5.87	11	<1	<2	<1	295	<.2	<.5	<.5	13	12.44	.105	2	14	2.79	168	.001	8	.32	.017	.14	<1	<1	8.8	<1	.87	1
1518	3.4	75	10	78	.1	60	31	1024	6.97	12	<1	<2	1	246	<.2	<.5	<.5	16	9.43	.156	3	9	2.21	181	.001	5	.38	.018	.14	<1	<1	7.5	<1	1.53	1
1519	3.6	118	10	61	.1	53	37	1547	8.45	7	<1	<2	<1	267	.2	<.5	<.5	18	7.66	.133	2	7	2.42	133	.001	4	.36	.024	.14	1	<1	8.3	<1	2.57	1
1520	2.7	133	12	85	.2	62	37	1489	7.75	7	1	<2	1	284	.2	<.5	<.5	15	7.03	.136	2	7	2.37	91	.001	2	.38	.018	.15	1	<1	7.5	<1	2.50	1
RE 1520	2.8	132	10	86	.2	62	37	1500	7.79	7	<1	<2	1	286	.3	<.5	<.5	16	7.06	.136	2	7	2.40	90	.001	3	.38	.017	.15	1	<1	7.6	<1	2.49	1
1521	3.0	128	8	84	.1	106	44	1532	8.12	8	1	<2	1	279	.3	.5	<.5	18	6.27	.122	1	16	2.81	60	.001	6	.37	.013	.18	2	<1	7.7	1	2.48	1
1522	1.8	103	10	105	.2	129	45	425	6.71	11	2	<2	1	51	<.2	.8	<.5	24	.97	.211	6	27	.92	50	.001	5	.51	.016	.22	2	1	5.2	<1	3.67	1
1523	5.8	107	9	155	.2	143	44	357	7.40	33	3	<2	1	74	.6	2.1	.6	25	1.58	.183	5	30	1.03	48	.001	3	.47	.013	.20	2	7	4.5	1	5.05	1
1524	2.0	115	9	150	.2	58	43	200	9.39	32	1	<2	1	55	.5	2.8	<.5	17	.91	.277	7	11	.29	27	.001	1	.61	.011	.18	3	9	3.3	3	8.23	1
1526	3.2	77	9	160	.2	46	39	313	9.14	26	1	<2	2	57	.5	2.2	<.5	13	.87	.283	7	10	.42	30	.002	1	.51	.008	.19	3	6	2.9	2	7.23	1
1527	4.5	45	9	120	.1	39	42	454	8.37	19	1	<2	1	68	.3	1.6	<.5	13	1.15	.385	6	9	.58	33	.002	3	.60	.018	.21	2	5	3.4	1	5.56	1
1528	3.4	63	5	144	<.1	49	45	591	8.53	12	1	<2	1	63	<.2	<.5	<.5	17	1.55	.242	6	14	.94	44	.001	3	.49	.024	.18	2	3	4.3	<1	4.72	1
1529	1.6	64	6	141	.1	50	44	723	10.00	13	1	<2	1	49	.2	1.2	<.5	18	1.29	.206	6	12	.93	46	.002	<1	.41	.024	.15	2	6	4.7	1	5.61	1
1530	1.6	57	4	143	<.1	39	36	573	6.86	9	1	<2	1	60	<.2	.5	<.5	18	1.56	.314	8	12	.87	64	.001	2	.49	.033	.19	1	4	4.2	<1	3.21	1
1531	1.5	82	7	94	.1	46	48	573	8.31	10	1	<2	1	57	<.2	.8	<.5	21	1.43	.204	6	12	.77	47	.002	2	.40	.029	.14	2	6	5.0	<1	5.27	1
1532	1.6	207	3	166	.1	59	42	1464	7.91	6	1	<2	1	59	<.2	.5	<.5	26	1.55	.192	8	11	1.32	188	.001	4	.78	.020	.14	2	1	7.1	<1	1.08	2
1533	.8	146	5	92	.1	63	52	1222	7.43	13	1	<2	1	53	<.2	2.0	<.5	24	1.32	.251	8	9	.96	87	.001	2	.62	.036	.14	1	1	6.5	1	2.55	2
1534	1.4	155	2	110	.1	56	44	1612	8.31	7	1	<2	2	43	<.2	<.5	<.5	23	1.10	.191	8	9	1.17	118	.001	1	.83	.014	.09	1	1	6.4	1	1.26	2
1535	2.0	172	6	105	.1	53	48	1456	10.41	20	1	<2	2	55	<.2	1.7	<.5	28	1.59	.173	6	9	1.13	51	.001	<1	.84	.033	.10	2	1	6.5	3	4.76	1
STANDARD C3	26.9	67	34	171	5.4	36	12	803	3.37	56	26	2	20	29	21.7	15.8	22.5	81	.60	.094	21	176	.62	159	.086	21	1.76	.037	.16	16	1	4.5	<1	.03	6
STANDARD G-2	1.5	3	2	46	<.1	7	4	562	2.07	<1	3	<2	4	72	<.2	<.5	<.5	43	.68	.103	10	82	.63	237	.127	3	.92	.078	.49	2	<1	2.7	1	<.01	4

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 2 2000 DATE REPORT MAILED: Oct 12/00 SIGNED BY: D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003584R Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0932	4.1	67	10	96	.3	56	17	534	3.52	105	2	<2	3	70	.4	6.6	<.5	30	2.01	.100	9	16	.87	282	.002	8	.44	.016	.18	4	<1	4.2	<1	.80	2
0933	1.4	49	3	99	.1	40	22	1616	5.25	76	1	<2	5	51	.4	.8	<.5	10	1.53	.044	16	14	1.19	146	.006	14	.53	.022	.28	2	<1	4.1	<1	.15	2
0934	1.1	57	8	40	.3	91	36	1650	5.00	184	2	<2	<1	233	.5	.8	<.5	18	7.42	.086	3	18	3.00	81	.011	5	.34	.014	.20	2	<1	7.0	<1	.43	1
0935	2.1	76	5	65	.3	70	29	1724	5.73	120	2	<2	<1	204	.4	4.1	.5	18	7.69	.115	3	16	3.00	99	.013	11	.39	.013	.21	2	<1	7.3	<1	.51	2
0936	.8	59	7	49	.2	46	26	1421	4.75	104	2	<2	1	161	.3	5.1	<.5	14	6.32	.092	2	11	2.19	118	.008	5	.28	.012	.15	3	<1	5.6	<1	.75	1
0937	1.3	49	4	49	.2	35	17	950	3.44	25	1	<2	1	151	<.2	2.0	<.5	10	5.90	.070	4	11	1.97	69	.005	7	.25	.011	.14	2	<1	4.9	<1	.33	1
0938	1.1	81	5	83	.3	99	35	1155	5.61	19	1	<2	<1	198	<.2	2.6	<.5	12	8.17	.092	2	12	2.60	105	.005	6	.30	.011	.15	1	<1	6.5	<1	1.19	1
0939	1.6	95	4	64	.3	178	41	1174	5.79	29	1	<2	<1	292	<.2	1.7	<.5	12	10.60	.081	2	23	3.71	83	.007	6	.37	.011	.14	1	<1	9.6	<1	.69	1
0940	2.5	72	281	531	1.1	162	35	1762	6.57	205	1	<2	1	273	5.5	2.9	2.1	13	12.42	.060	1	25	3.51	191	.008	4	.30	.012	.16	1	<1	8.7	<1	.95	1
0941	2.8	69	808	740	1.7	98	33	1680	6.91	142	2	<2	<1	240	7.7	2.2	3.0	16	9.78	.141	2	17	2.59	148	.021	6	.38	.014	.21	1	<1	8.2	<1	.97	2
0942	3.2	86	13	80	.3	66	34	1170	7.60	37	1	<2	1	250	.3	.5	<.5	12	8.55	.178	2	6	2.32	96	.011	7	.34	.010	.14	1	<1	6.9	1	2.28	2
0943	7.8	183	12	123	.3	118	56	1104	9.91	25	1	<2	<1	169	<.2	<.5	<.5	22	4.37	.171	2	16	1.96	116	.004	4	.51	.021	.16	1	<1	7.2	<1	4.51	2
0944	2.3	115	10	75	.2	128	38	1247	7.13	2	1	<2	1	220	<.2	.5	<.5	15	4.99	.093	2	26	2.11	125	.007	5	.41	.020	.19	2	<1	6.2	<1	2.27	1
0945	1.9	100	6	98	.2	129	32	1078	6.83	2	1	<2	1	141	<.2	<.5	<.5	14	3.69	.092	2	31	1.94	119	.005	3	.44	.018	.19	2	<1	5.6	<1	1.64	2
RE 0945	1.8	101	6	99	.2	125	31	1084	6.69	1	2	<2	2	142	<.2	<.5	.7	16	3.73	.092	3	32	1.96	121	.006	7	.45	.019	.20	2	<1	5.8	<1	1.61	2
0946	1.0	85	5	94	.1	97	31	602	5.54	10	1	<2	<1	88	<.2	<.5	<.5	13	1.78	.116	2	18	1.23	173	.006	3	.45	.019	.22	2	1	4.1	<1	2.53	2
0947	3.5	116	11	154	.2	63	44	144	9.23	46	1	<2	1	44	.6	5.5	<.5	28	.80	.239	2	12	.29	102	.019	3	.59	.022	.26	2	17	3.4	5	8.94	2
0948	5.9	149	7	137	.2	52	36	366	7.23	16	1	<2	<1	44	.3	1.6	<.5	21	.74	.251	4	9	.33	103	.022	4	.57	.028	.24	2	3	3.3	<1	5.98	2
0950	2.6	124	4	146	.1	45	39	348	4.54	6	1	<2	2	54	<.2	<.5	<.5	20	.86	.290	6	8	.44	178	.016	9	.53	.040	.21	1	1	4.0	<1	1.85	2
0985	5.0	124	4	266	.1	60	46	827	5.83	8	1	<2	<1	59	.4	<.5	<.5	22	1.21	.261	6	8	.81	197	.014	5	.54	.043	.22	1	1	5.5	<1	1.15	3
0986	.9	180	2	81	.1	69	54	1612	8.32	8	1	<2	1	46	<.2	<.5	<.5	21	1.23	.191	3	6	1.26	85	.005	3	.26	.021	.08	<1	1	6.5	1	1.01	3
0987	2.1	164	7	163	<.1	69	53	918	11.27	57	<1	<2	<1	50	.2	3.1	<.5	25	1.40	.139	2	11	.91	76	.005	3	.42	.053	.13	1	2	5.4	3	7.88	2
0988	3.3	174	9	408	.1	79	55	804	12.06	72	<1	<2	<1	50	1.1	2.9	<.5	32	1.48	.156	3	16	.84	87	.010	3	.51	.066	.13	1	3	6.4	4	9.28	3
0989	1.9	145	6	141	.1	71	54	700	10.87	44	<1	<2	<1	50	.3	1.7	<.5	24	1.56	.165	3	11	.70	88	.009	4	.47	.068	.13	1	2	5.8	3	8.70	2
0990	3.5	138	5	272	.1	50	40	1045	7.47	20	<1	<2	1	55	.5	.8	<.5	25	1.50	.197	3	12	.81	132	.010	<1	.58	.088	.13	2	1	5.5	<1	3.75	3
0991	2.3	171	8	213	.1	68	55	943	10.34	61	<1	<2	<1	40	.6	3.6	<.5	23	1.00	.184	3	11	.58	84	.012	<1	.51	.079	.13	1	1	5.3	2	7.46	3
0992	1.9	113	4	107	<.1	73	45	1233	8.65	19	<1	<2	<1	49	<.2	.6	<.5	20	1.33	.153	3	13	1.08	151	.007	5	.54	.090	.14	1	1	5.3	<1	3.09	3
0993	1.8	159	5	105	.2	86	56	1422	9.16	13	<1	<2	1	75	<.2	<.5	<.5	21	1.97	.159	2	8	1.24	139	.008	1	.56	.083	.13	1	2	6.6	1	3.25	2
0994	2.3	164	7	139	.1	89	60	1675	10.22	30	<1	<2	<1	112	.3	.6	<.5	26	3.42	.135	2	9	1.70	140	.009	7	.59	.094	.15	2	7	7.3	3	4.26	2
0995	1.5	164	6	123	.2	126	65	1160	8.20	33	1	<2	<1	83	.2	1.1	<.5	22	2.55	.141	2	17	1.46	144	.007	5	.56	.063	.20	1	4	5.3	3	3.81	2
0996	1.7	41	4	53	<.1	35	15	100	2.80	15	2	<2	2	19	.2	<.5	<.5	7	.23	.044	8	16	.21	145	.004	4	.47	.031	.22	3	1	1.6	<1	1.94	2
0997	1.5	36	11	65	<.1	29	10	47	4.76	41	1	<2	3	17	.2	2.6	<.5	2	.03	.011	8	12	.06	61	.001	3	.26	.013	.11	9	2	.9	<1	4.93	1
0998	2.0	21	11	121	<.1	26	11	37	3.60	22	2	<2	3	10	.3	1.1	.5	1	.08	.031	9	13	.07	92	.002	5	.34	.016	.16	3	1	.9	<1	3.72	1
0999	3.1	42	16	137	.1	70	25	150	5.87	57	2	<2	2	16	.6	2.1	.5	4	.30	.035	5	16	.25	72	.003	2	.37	.016	.16	4	3	1.4	<1	5.65	1
1000	1.1	134	3	168	.1	133	53	702	4.85	25	2	<2	1	62	.4	<.5	<.5	15	1.65	.088	2	20	.98	199	.008	6	.43	.017	.18	2	<1	5.3	<1	2.56	1
STANDARD C3	28.0	70	43	173	5.5	37	12	818	3.44	58	24	<2	21	28	23.0	16.5	24.1	83	.61	.094	19	176	.64	161	.088	23	1.85	.046	.18	17	1	4.6	<1	.03	8
STANDARD G-2	1.6	2	3	46	<.1	8	4	561	2.09	1	2	<2	3	82	<.2	<.5	<.5	43	.71	.105	7	83	.64	253	.131	2	1.04	.117	.57	2	<1	2.6	<1	<.01	6

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 2 2000 DATE REPORT MAILED: Oct 13/00 SIGNED BY.....C.L.....D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
1501	3.4	114	5	237	.1	117	40	412	3.27	19	4	<2	1	49	.7	.8	<.5	18	1.26	.112	5	16	.68	108	.001	6	.34	.014	.16	2	<1	3.5	<1	1.52	<1
1502	2.4	50	7	119	.2	61	21	330	4.18	12	2	<2	3	30	<.2	.5	<.5	8	.68	.053	8	16	.48	94	<.001	5	.30	.010	.14	3	1	2.2	<1	2.77	<1
1503	3.8	112	4	94	.1	264	70	1581	9.17	27	4	<2	1	36	<.2	<.5	.5	16	.85	.147	5	27	1.21	57	.002	7	.36	.016	.18	2	<1	5.0	1	2.53	1
1504	2.2	39	9	69	.1	76	22	423	3.94	7	2	<2	5	20	<.2	1.1	<.5	8	.38	.066	12	19	.42	97	<.001	3	.36	.009	.12	3	<1	2.7	<1	1.51	1
RE 1504	2.2	39	9	71	.1	75	20	422	3.94	7	2	<2	5	20	<.2	1.0	<.5	8	.38	.065	12	19	.42	96	<.001	4	.36	.010	.12	3	<1	2.7	1	1.49	1

Sample type: CORE PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data__ FA ____

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) 1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003051R Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: R. Hall

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0729	1.8	88	12	139	.5	56	53	2123	11.12	114	<1	<2	2	125	.8	1.4	1.1	17	3.70	.164	3	7	1.89	70	.001	2	.41	.020	.18	1	<1	6.8	<1	4.00	2
0730	2.2	26	73	38	1.9	88	80	1004	10.98	513	<1	4	4	188	<.2	.5	6.0	14	3.16	.305	4	6	.88	55	.003	3	.49	.016	.29	1	1	7.0	<1	9.87	2
0731	1.9	38	39	40	1.3	60	50	838	12.71	433	1	10	3	166	.2	<.5	6.8	10	2.96	.356	4	7	.83	50	.001	7	.50	.015	.27	1	2	5.5	1	13.15	3
0732	3.2	8	5	29	.2	58	48	1822	4.83	176	2	<2	2	313	.6	<.5	1.2	17	5.15	.356	4	4	1.74	156	.002	10	.55	.019	.31	1	<1	8.2	<1	1.60	2
0733	1.2	27	19	21	.5	68	64	662	8.54	304	<1	3	1	162	<.2	<.5	4.0	17	2.66	.434	4	6	.59	57	.002	4	.59	.021	.31	2	1	5.9	1	8.31	3
0734	2.3	21	27	32	.9	79	59	1253	10.23	454	<1	7	2	239	<.2	.8	4.4	17	4.07	.355	3	7	1.17	62	.002	6	.56	.020	.31	1	1	8.3	1	8.93	2
0735	1.4	14	19	21	.6	59	53	956	7.75	328	<1	4	1	204	<.2	<.5	3.4	14	3.51	.464	3	6	.86	63	.002	5	.61	.020	.31	1	1	6.6	<1	7.01	2
0736	2.2	26	54	26	2.4	71	64	1061	9.48	283	<1	25	2	207	<.2	1.8	5.5	18	3.71	.390	3	7	1.06	66	.002	4	.59	.021	.33	1	1	7.4	2	8.32	2
0737	1.5	95	71	86	2.7	89	68	1395	16.17	274	1	26	3	110	<.2	3.1	6.7	17	2.25	.204	3	8	1.10	48	.001	1	.40	.026	.22	1	2	7.2	2	13.42	3
0738	2.3	20	8	53	.3	52	60	1637	9.86	159	<1	<2	3	256	.5	2.4	3.6	21	4.36	.346	4	6	1.55	88	.001	3	.44	.028	.22	<1	<1	11.7	1	6.32	2
0739	1.0	153	5	88	.2	68	58	1524	10.64	76	<1	<2	2	63	.3	.9	.6	19	1.70	.198	5	8	1.14	73	.002	<1	.38	.049	.17	1	<1	5.8	<1	5.48	2
0740	2.2	212	5	96	.3	63	49	2074	9.27	38	<1	<2	2	67	.2	.7	<.5	21	1.85	.178	6	10	1.51	190	.002	<1	.48	.061	.19	<1	<1	7.1	<1	1.13	2
0741	.9	182	2	91	.2	56	49	1835	9.28	16	<1	<2	<1	51	<.2	.6	<.5	20	1.35	.207	7	6	1.37	140	.001	<1	.40	.056	.15	1	<1	6.1	<1	1.33	2
0742	1.5	158	3	93	.2	40	39	1610	8.08	9	<1	<2	4	89	.2	<.5	<.5	19	2.31	.155	4	7	1.64	169	.001	<1	.48	.057	.16	<1	<1	6.5	<1	.88	1
RE 0742	1.7	155	3	88	.2	43	39	1601	8.09	9	<1	<2	<1	82	.2	<.5	<.5	20	2.34	.157	4	7	1.62	171	.001	4	.48	.054	.15	<1	<1	6.4	<1	.87	2
0743	.9	192	2	73	.1	57	47	1142	7.68	21	<1	<2	<1	66	.2	<.5	<.5	16	1.96	.147	3	7	1.31	119	.001	<1	.40	.065	.14	1	<1	5.2	<1	1.89	2
0744	1.7	129	3	92	.1	69	51	1830	8.86	12	<1	<2	2	80	<.2	<.5	<.5	19	2.35	.135	3	10	1.68	148	.001	3	.38	.055	.15	<1	<1	6.8	<1	1.49	2
0745	1.1	165	2	95	.2	50	48	1541	9.79	19	<1	<2	2	82	<.2	<.5	<.5	28	2.21	.183	5	6	1.59	111	.001	6	.38	.054	.15	<1	1	7.7	<1	2.43	2
0746	1.6	101	2	97	.2	54	48	1132	7.92	5	<1	<2	2	86	.2	<.5	<.5	32	2.35	.198	7	7	1.58	170	.002	3	.45	.046	.15	<1	<1	6.7	<1	.87	3
0747	2.7	261	9	218	.3	106	66	667	16.04	54	<1	<2	1	63	.4	2.4	.6	16	1.44	.172	2	10	1.04	46	.001	<1	.36	.020	.18	2	9	4.1	3	12.33	3
0854	.9	5	3	32	.1	62	23	2043	4.10	142	2	<2	1	173	.4	.8	<.5	16	5.55	.090	3	24	1.92	62	.001	6	.26	.008	.18	4	<1	5.7	<1	.84	<1
0855	13.2	7	13	23	.2	80	16	969	3.47	215	3	<2	4	100	.7	1.5	2.1	46	2.59	.173	5	30	.94	97	<.001	7	.45	.012	.20	2	<1	4.2	<1	2.31	1
0856	2.6	7	34	37	1.1	179	57	3068	11.18	664	2	4	2	197	<.2	1.5	8.5	13	6.87	.120	2	18	2.99	54	.001	2	.31	.007	.20	3	1	9.8	1	6.58	2
0857	3.8	12	10	49	.4	175	50	1686	7.98	392	1	<2	<1	200	<.2	.9	3.6	13	7.47	.088	2	21	2.64	92	.001	2	.33	.009	.20	2	<1	7.9	<1	3.88	1
0858	6.8	18	43	51	1.5	166	69	2203	10.43	395	1	8	1	183	<.2	1.8	6.2	18	6.37	.175	2	12	2.17	95	.001	4	.40	.011	.26	2	<1	7.9	<1	6.60	2
0859	4.8	59	27	55	.8	103	58	1482	9.87	383	<1	3	4	152	<.2	1.8	2.9	13	3.78	.155	2	10	1.49	85	.001	2	.38	.011	.23	3	<1	5.9	<1	7.04	2
0860	.7	20	22	23	.5	99	36	720	5.08	348	1	<2	6	85	<.2	<.5	1.7	7	2.00	.053	3	10	.67	83	.001	5	.35	.012	.22	3	<1	2.4	<1	4.84	1
0861	3.5	21	17	48	.1	55	18	1515	4.38	221	2	<2	5	159	.7	<.5	.6	7	3.37	.055	4	11	1.23	83	.001	4	.30	.012	.20	1	<1	4.2	<1	2.53	<1
0862	2.6	51	19	33	.4	95	57	834	6.52	449	1	<2	3	71	<.2	<.5	1.8	6	1.61	.041	4	12	.58	64	.001	5	.37	.014	.23	3	<1	2.3	<1	6.87	1
0863	1.2	62	9	36	<.1	46	21	441	3.41	154	2	<2	3	31	.4	<.5	<.5	5	.57	.038	9	9	.54	108	.001	5	.36	.018	.22	2	<1	1.4	<1	2.44	1
0864	2.1	66	10	68	.2	124	47	742	5.61	413	1	<2	2	116	<.2	<.5	.8	11	1.60	.070	3	22	.90	70	.001	4	.41	.018	.25	3	<1	3.4	<1	4.83	1
0865	.8	41	6	67	.1	50	15	1118	4.45	146	2	<2	3	233	.5	<.5	<.5	9	3.25	.057	5	11	1.75	111	.001	5	.36	.017	.23	2	<1	3.0	<1	1.53	<1
0866	2.5	37	6	68	.1	114	29	1352	5.96	201	1	<2	<1	245	.7	.6	<.5	15	4.83	.081	6	27	2.72	88	.001	7	.34	.016	.20	2	<1	5.4	<1	.53	1
0867	2.0	5	<2	9	<.1	16	3	539	1.29	48	<1	<2	6	79	<.2	<.5	<.5	6	1.08	.024	14	15	.49	87	<.001	7	.34	.018	.21	5	<1	2.4	<1	.29	1
0868	1.8	22	7	31	<.1	25	10	1070	3.13	98	1	<2	1	102	.3	<.5	<.5	6	2.27	.033	7	13	1.12	85	.001	6	.32	.015	.19	3	<1	2.2	<1	1.14	1
STANDARD C3	27.2	71	36	181	5.5	39	13	838	3.50	58	25	<2	22	31	23.3	15.9	23.3	84	.62	.099	20	186	.65	166	.093	24	1.86	.048	.18	16	1	4.4	<1	.03	8
STANDARD G-2	1.5	2	3	47	<.1	8	4	560	2.08	1	2	<2	4	74	<.2	<.5	<.5	43	.69	.104	8	84	.63	233	.134	3	.96	.087	.50	2	<1	2.6	<1	<.01	5

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 2 2000 DATE REPORT MAILED: Oct 13/00 SIGNED BY: D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0869	1.1	33	8	35	<.1	38	13	226	2.95	60	1	<2	1	32	<.2	<.5	<.5	5	.64	.053	9	9	.58	102	.001	8	.31	.015	.19	2	<1	1.4	<1	1.51	1
0870	2.6	33	8	33	<.1	40	13	235	4.36	74	1	<2	1	37	.2	1.6	<.5	4	.66	.034	6	15	.60	94	.001	7	.31	.016	.20	4	4	1.4	<1	2.97	1
0873	2.2	43	6	32	<.1	39	14	223	4.39	106	1	<2	1	27	.3	3.4	<.5	5	.50	.035	6	14	.43	80	.001	8	.34	.016	.21	3	8	1.1	<1	3.62	<1
0874	.9	34	4	58	.1	70	21	1318	4.87	114	1	<2	15	418	.3	1.2	<.5	9	8.40	.114	4	11	3.40	121	.001	5	.33	.017	.21	1	1	5.5	<1	1.07	<1
0875	3.1	6	5	60	.3	115	33	1977	6.74	234	1	<2	10	744	.8	1.3	<.5	16	15.56	.173	3	21	4.83	112	.002	4	.32	.016	.21	2	1	10.6	<1	1.41	<1
0876	2.0	25	75	63	2.4	194	69	307	11.76	554	<1	5	<1	141	<.2	3.1	7.9	19	1.86	.308	3	15	.47	46	.002	3	.54	.017	.29	2	5	7.8	<1	11.43	2
0877	3.3	28	161	64	6.7	170	52	62	15.59	710	2	19	<1	72	<.2	2.5	14.3	14	.81	.272	3	15	.08	19	.002	10	.43	.015	.24	2	4	3.2	<1	17.12	1
0878	3.2	43	154	93	6.0	132	54	27	32.94	779	<1	8	1	35	<.2	1.7	29.3	9	.38	.156	1	9	.01	8	.002	<1	.26	.010	.14	3	25	2.0	1	38.00	<1
0879	6.4	33	66	74	2.5	121	66	30	11.86	414	1	4	<1	71	<.2	2.4	19.5	17	.98	.431	4	10	.02	32	.002	7	.58	.015	.29	2	5	2.1	<1	13.16	1
0880	4.8	38	59	80	2.1	95	65	28	13.59	508	<1	4	1	90	.2	1.0	22.7	20	.93	.413	5	7	.02	31	.002	8	.57	.015	.31	2	2	2.4	<1	14.35	1
0882	1.8	31	50	40	2.1	145	84	103	14.36	681	<1	7	<1	115	<.2	1.9	18.3	19	1.25	.458	5	7	.10	39	.002	3	.51	.015	.26	2	4	3.1	<1	14.48	2
0883	1.5	14	31	22	1.5	135	70	844	9.42	549	1	7	<1	236	<.2	.6	4.8	23	3.13	.498	4	6	.78	65	.002	9	.60	.022	.34	2	2	7.7	<1	8.91	3
0884	1.2	13	40	21	1.8	179	91	1333	10.85	767	1	8	2	305	<.2	<.5	5.6	23	4.17	.687	4	6	.98	60	.002	4	.63	.020	.36	3	1	8.4	<1	9.76	2
0885	2.1	50	116	41	6.7	121	84	674	14.99	859	1	66	<1	103	<.2	.5	8.9	18	1.74	.251	3	8	.52	47	.002	7	.51	.017	.29	2	3	6.1	<1	15.05	2
0886	1.6	56	59	43	1.8	110	70	1438	10.09	680	1	19	<1	149	<.2	1.5	3.2	19	3.29	.214	2	8	1.03	67	.002	9	.50	.016	.27	2	1	9.8	<1	9.14	2
0887	1.4	69	39	29	.8	169	87	921	10.51	852	<1	10	<1	111	<.2	.6	2.7	16	2.36	.152	3	16	.73	60	.001	3	.51	.020	.28	2	1	7.8	<1	9.99	1
0888	2.1	50	29	29	.6	135	97	1250	10.20	851	<1	5	<1	160	<.2	1.2	2.2	18	3.27	.235	3	6	1.00	77	.002	5	.48	.015	.26	2	1	9.8	<1	9.08	1
0889	2.5	96	127	54	2.7	165	106	2082	19.65	1129	1	38	1	152	<.2	2.0	6.8	20	3.07	.152	3	11	1.26	60	.002	6	.42	.015	.24	2	2	10.3	<1	18.00	2
0890	16.4	39	40	53	.6	120	72	726	11.28	439	<1	6	<1	73	<.2	1.8	3.5	17	1.33	.181	3	13	.48	32	.001	5	.50	.019	.30	2	2	6.8	1	10.40	1
RE 0890	15.7	39	39	56	.6	122	74	737	11.26	445	<1	7	1	77	<.2	2.0	3.9	19	1.33	.184	2	14	.48	33	.002	5	.51	.018	.30	2	2	7.0	1	10.60	1
0891	1.6	36	38	50	.9	87	58	992	10.05	650	1	12	<1	135	<.2	3.1	3.4	17	2.64	.258	3	9	.77	46	.001	6	.52	.018	.34	2	1	7.4	<1	9.62	2
0892	4.0	31	46	42	1.2	85	57	2064	13.30	842	1	15	1	144	<.2	2.4	2.8	17	3.80	.165	2	7	1.29	33	.001	1	.38	.013	.23	2	1	8.5	<1	12.00	1
0893	1.7	40	44	34	1.2	75	51	2106	9.86	527	<1	13	1	200	<.2	2.0	2.2	20	4.66	.256	3	5	1.41	79	.002	6	.52	.019	.32	2	1	10.0	<1	7.85	1
0894	1.7	41	29	46	.6	93	73	1306	11.92	650	<1	5	1	201	<.2	.8	2.8	16	3.72	.311	3	7	1.22	64	.002	11	.49	.017	.29	1	1	9.8	<1	10.32	2
0898	3.6	36	27	38	.4	85	64	1669	10.03	607	<1	3	<1	224	<.2	<.5	2.4	19	4.54	.269	4	5	1.43	79	.002	4	.51	.019	.31	1	<1	9.8	<1	8.15	1
0899	1.5	48	57	86	1.2	53	43	1730	11.59	433	<1	14	<1	172	<.2	.9	2.9	15	3.13	.281	3	6	1.35	67	.001	2	.47	.018	.28	1	1	8.4	<1	8.07	1
0900	1.4	76	3	121	.1	48	40	1780	8.19	92	<1	<2	1	93	.5	<.5	<.5	14	1.91	.202	3	7	1.53	136	.001	4	.42	.018	.22	2	<1	6.9	<1	1.93	2
STANDARD C3	27.0	70	36	176	5.4	38	12	816	3.37	58	24	2	19	27	23.0	16.3	23.1	82	.61	.097	19	182	.62	161	.089	25	1.83	.043	.17	15	1	4.5	<1	.04	8
STANDARD G-2	1.4	2	2	45	<.1	7	4	539	2.01	1	2	<2	3	70	<.2	<.5	<.5	42	.67	.098	7	76	.61	225	.128	4	.91	.083	.47	2	<1	2.6	<1	<.01	5

Sample type: CORE PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6

(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003184R Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ken Lord

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0816	2.4	153	10	128	.3	49	22	971	5.26	555	5	<2	4	150	.3	2.3	.5	13	2.28	.067	9	12	1.23	82	<.001	11	.30	.015	.17	4	<1	6.3	<1	2.57	<1
0817	5.5	7	5	34	.1	56	11	1736	3.85	180	1	<2	5	351	<.2	.8	<.5	22	5.66	.195	5	10	2.11	130	<.001	12	.35	.014	.20	2	<1	5.4	<1	1.13	1
0818	4.6	5	7	38	.3	96	38	2264	7.70	366	6	<2	2	341	.3	<.5	<.5	17	7.62	.112	3	14	2.95	78	.001	13	.35	.012	.21	2	<1	8.3	<1	4.20	1
0819	5.3	16	20	33	1.1	112	58	1714	8.65	421	1	6	1	269	.2	.7	2.0	17	6.63	.121	2	17	2.66	86	.001	11	.44	.012	.26	1	<1	8.5	<1	5.97	1
0820	9.1	20	112	13	5.1	255	80	526	18.75	1126	1	17	1	115	.2	.7	11.9	11	2.04	.069	4	17	.88	55	.002	11	.27	.004	.15	2	<1	3.4	<1	18.00	2
0821	5.4	27	190	14	12.2	396	115	141	31.95	1770	<1	44	2	37	.4	1.2	26.0	11	.61	.057	4	11	.20	13	.002	9	.24	.001	.12	2	<1	1.6	<1	35.00	<1
0822	2.6	15	273	9	8.5	402	114	38	32.50	1852	<1	16	2	13	.3	1.8	31.6	9	.18	.044	2	14	.03	7	.003	7	.21	<.001	.10	4	<1	.3	<1	34.00	<1
0823	7.8	14	62	26	4.0	232	73	1229	18.63	1128	2	10	2	152	<.2	<.5	19.5	12	3.96	.058	3	14	1.74	51	.001	6	.27	.002	.15	1	<1	5.6	<1	17.00	2
0824	5.3	9	114	8	4.9	189	53	313	19.05	1146	2	5	5	39	.2	.5	23.3	6	1.02	.027	5	9	.37	28	.002	9	.27	.002	.15	2	<1	1.9	<1	18.00	1
0825	.7	1	9	4	.5	62	18	164	4.65	372	4	3	13	22	<.2	.5	.8	4	.47	.022	10	5	.16	78	.001	6	.30	.004	.19	1	<1	1.6	<1	5.52	<1
0826	2.9	1	12	11	1.0	83	25	96	6.19	489	3	4	9	16	<.2	<.5	1.1	1	.33	.007	6	3	.12	40	<.001	4	.11	<.001	.07	1	<1	1.0	<1	7.23	<1
0827	1.9	3	5	6	.3	60	20	85	5.14	422	3	2	9	14	<.2	.6	<.5	6	.30	.007	11	4	.11	62	<.001	4	.29	.004	.18	1	<1	1.1	<1	5.98	<1
0828	3.5	9	154	29	6.1	182	69	1813	14.70	852	2	24	2	174	.2	<.5	17.4	14	5.50	.038	2	20	2.29	65	.001	7	.35	.005	.21	1	<1	8.4	<1	13.00	2
0829	2.0	8	9	53	.1	126	48	2915	7.80	256	1	<2	1	300	.2	<.5	2.4	14	12.12	.070	<1	14	3.80	99	.001	7	.31	.007	.22	<1	<1	12.5	<1	1.65	1
0830	5.3	12	48	44	1.1	154	69	2471	13.11	536	<1	6	1	230	<.2	.7	6.5	20	7.62	.142	1	14	2.73	90	.001	7	.43	.008	.25	1	<1	9.3	<1	7.82	1
RE 0830	5.2	12	48	44	1.1	154	70	2436	12.94	542	1	6	1	236	.2	<.5	6.8	20	7.74	.146	1	14	2.70	91	.001	10	.43	.008	.25	<1	<1	9.2	<1	7.92	2
0831	6.6	19	59	38	2.3	107	53	1900	14.41	579	1	9	1	237	<.2	<.5	8.8	16	5.90	.172	2	7	2.06	79	.002	9	.35	.004	.22	1	<1	8.4	<1	12.00	2
0832	3.2	24	32	39	.8	96	51	1697	12.69	383	1	<2	1	284	.2	<.5	6.0	21	6.62	.170	1	8	2.50	82	.002	8	.50	.007	.29	1	<1	9.2	<1	8.94	2
0833	3.0	10	9	40	.1	78	27	2198	6.62	283	1	<2	2	320	<.2	<.5	.7	15	7.52	.168	2	9	2.68	92	.002	7	.39	.010	.23	1	<1	8.5	<1	2.69	1
0834	2.7	1	3	12	<.1	29	11	1221	2.42	118	2	<2	6	178	<.2	<.5	<.5	9	3.22	.089	10	6	1.22	91	<.001	8	.34	.008	.21	1	<1	5.5	<1	.90	1
0835	1.4	7	5	52	<.1	143	50	1783	5.71	281	2	<2	18	415	<.2	.6	.6	18	9.10	.112	2	16	3.48	185	.001	7	.39	.014	.22	<1	<1	13.0	<1	1.05	1
0836	.9	6	5	35	<.1	36	16	1864	4.70	107	1	<2	5	378	<.2	<.5	<.5	10	7.52	.047	5	5	2.96	120	<.001	5	.35	.016	.22	<1	<1	7.9	<1	.62	1
0837	2.4	10	7	51	<.1	103	50	2357	6.37	260	1	<2	1	448	.2	<.5	<.5	18	11.99	.129	2	6	3.63	109	.001	7	.38	.019	.23	1	<1	10.8	<1	.40	1
0841	1.8	1	4	45	<.1	177	82	2227	5.38	455	<1	<2	1	379	<.2	.7	<.5	23	8.92	.142	3	33	3.12	128	.001	8	.43	.016	.26	<1	<1	13.3	<1	.41	1
0842	.8	3	5	52	<.1	160	49	2499	6.19	341	<1	<2	1	481	<.2	.7	<.5	19	13.24	.096	2	29	4.28	78	.001	6	.32	.014	.20	<1	<1	13.2	1	.13	1
0843	1.6	6	3	43	<.1	119	48	2349	6.63	382	<1	<2	1	392	<.2	<.5	<.5	18	8.88	.151	2	11	3.05	80	.001	8	.38	.012	.23	<1	<1	10.3	<1	1.20	1
0844	1.6	6	6	51	.1	120	60	2614	7.16	298	<1	<2	<1	406	<.2	<.5	.9	24	11.66	.143	2	18	3.63	73	.002	8	.35	.012	.21	1	<1	12.1	<1	1.42	1
0845	.6	9	6	46	<.1	44	30	2469	6.30	124	<1	<2	1	390	<.2	<.5	.5	25	8.97	.161	3	5	3.22	84	.001	9	.37	.013	.22	1	<1	10.8	<1	1.23	1
0846	.8	33	19	28	.5	105	59	1814	8.41	400	1	3	1	260	.2	1.1	2.9	23	6.10	.202	1	7	2.12	98	.001	9	.44	.010	.24	1	<1	9.0	<1	5.40	1
0847	.3	12	15	38	.2	100	59	2624	11.02	398	<1	<2	1	366	.3	.5	4.1	22	8.75	.145	2	6	3.22	90	.001	9	.37	.010	.21	<1	<1	10.6	<1	5.60	1
0848	.5	23	14	21	.4	167	84	1728	10.81	797	<1	3	1	236	<.2	<.5	4.6	23	4.96	.146	2	11	1.88	61	.001	9	.46	.012	.25	1	<1	9.3	<1	7.66	1
0849	.2	32	2	40	.1	66	51	2762	7.69	170	<1	<2	1	283	.2	<.5	<.5	20	4.95	.179	4	4	2.42	125	.001	7	.41	.013	.23	<1	<1	12.0	<1	.57	1
0850	.3	46	<2	62	.1	85	63	2584	11.06	135	<1	<2	2	92	.2	<.5	<.5	20	1.88	.176	8	5	2.36	111	.001	10	.47	.015	.20	1	<1	10.6	<1	.27	1
0901	<.2	63	<2	56	<.1	127	56	1868	8.39	169	1	<2	1	120	.2	<.5	<.5	16	2.81	.139	6	11	2.19	119	.001	7	.43	.017	.19	<1	<1	8.9	<1	.25	1
0902	1.2	118	5	84	.1	65	52	1184	11.37	30	1	<2	1	79	<.2	.5	<.5	34	2.80	.148	5	9	1.55	66	.001	7	.51	.037	.12	1	1	6.8	2	5.88	1
STANDARD C3	27.3	70	36	176	5.4	37	12	821	3.48	57	26	2	23	30	22.3	16.5	23.5	81	.61	.097	22	178	.64	162	.086	21	1.81	.039	.17	16	1	4.7	1	.03	6
STANDARD G-2	1.4	3	3	43	<.1	7	4	521	1.93	<1	3	<2	4	66	<.2	<.5	<.5	38	.61	.098	10	74	.59	225	.121	1	.85	.067	.45	2	<1	2.6	<1	.01	4

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: CORE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 2 2000 DATE REPORT MAILED: Oct 16/00 SIGNED BY: ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
0903	.7	106	2	73	.2	47	38	1203	7.67	8	<1	<2	1	84	.2	.8	<.5	36	2.78	.145	2	8	1.56	121	.001	<1	.62	.045	.11	1	<1	6.8	<1	1.63	2
0904	.8	95	<2	67	.1	48	35	1133	6.50	4	<1	<2	3	68	<.2	<.5	<.5	33	2.26	.152	2	10	1.37	125	.002	1	.82	.052	.12	<1	<1	6.3	<1	1.03	3
0905	1.3	97	3	66	.2	64	44	1039	9.32	18	<1	<2	2	105	<.2	1.0	<.5	36	4.05	.125	2	15	1.78	118	.002	1	1.13	.049	.15	1	<1	6.5	<1	4.33	3
0906	1.1	88	5	50	.2	80	52	845	11.91	46	2	<2	3	128	.2	1.8	<.5	20	4.34	.099	1	11	1.73	85	.001	<1	.59	.034	.12	1	1	5.1	3	8.82	1
RE 0906	1.1	88	6	50	.2	82	53	858	12.26	48	1	<2	<1	128	<.2	2.4	<.5	20	4.48	.101	1	11	1.75	93	.001	<1	.59	.037	.13	1	1	5.3	2	8.94	2
STANDARD C3	27.1	69	38	172	5.7	39	12	834	3.48	61	24	<2	19	30	25.7	15.4	23.9	85	.62	.098	19	176	.66	160	.093	22	1.97	.046	.18	15	1	4.5	<1	.03	9
STANDARD G-2	1.6	2	3	43	<.1	8	4	557	2.05	<1	2	<2	3	73	<.2	<.5	<.5	44	.68	.108	7	79	.64	239	.133	4	1.00	.088	.52	2	<1	2.7	<1	.01	6

Sample type: CORE PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data: ✓ FA ____

APPENDIX IX

ASSAY CERTIFICATES

PART 3 -- DIAMOND DRILL HOLE SLUDGE SAMPLE ASSAY CERTIFICATES

PART 3

ACME ANALYTICAL LABORATORIES LTD. (ISO 9002 Accredited Co.)
852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716

GEOCHEM PRECIOUS METALS ANALYSIS

Standard Drilling PROJECT CARIBOO 2000 File # A000463 Page 1

305 - 459 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Au** ppb	
M 580301	7	
M 580302	2	
M 580303	<2	
M 580304	2	
M 580305	<2	
M 580306	<2	
M 580307	<2	
M 580308	2	
M 580309	2	
M 580310	<2	
RE M 580310	<2	
RRE M 580310	<2	
M 580311	<2	
M 580312	49	
M 580313	10	BC 2K-2 SLUDGE
M 580314	22	
M 580315	5	
M 580316	12	
M 580317	5	
M 580318	3	
M 580319	12	
M 580320	5	—
M 580321	28	
M 580322	12	
RE M 580322	4	BC 2K-1 SLUDGE
RRE M 580322	2	
M 580323	13	
M 580324	29	
M 580325	28	
M 580326	3	
M 580327	6	
M 580328	4	
M 580329	3	
M 580330	21	
STANDARD AU-R	472	

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: FEB 11 2000 DATE REPORT MAILED: Feb 21/2000 SIGNED BY: C. P. ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data A

SAMPLE#	Au** ppb	
M 580331	12	
M 580332	25	
M 580333	18	
M 580334	14	
M 580335	7	
M 580336	14	
M 580337	18	
M 580338	23	
M 580339	21	
M 580340	29	
M 580341	39	
M 580342	14	
RE M 580342	14	
RRE M 580342	15	
M 580343	19	
M 580344	24	BC 2K-1
M 580345	28	
M 580346	29	
M 580347	34	
M 580348	23	
M 580349	37	
M 580350	13	
M 580351	26	
M 580352	26	
M 580353	12	
M 580354	4858	
RE M 580354	4092	
RRE M 580354	6103	
M 580355	143	
M 580356	82	BC 2K-3
M 580357	2249	
M 580358	2013	
M 580359	251	
M 580360	554	
M 580361	3016	
STANDARD AU-R	468	

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** ppb
M 580362	9338
M 580363	871
M 580364	411
M 580365	515
M 580366	298
M 580367	299
M 580368	439
M 580369	1712
M 580370	7563
M 580371	9027
M 580372	907
RE M 580372	857
RRE M 580372	879
M 580373	138
M 580374	16
M 580375	17
M 580376	2122
M 580377	23
M 580378	1481
M 580379	528
M 580380	98
M 580381	668
M 580382	10048
M 580383	772
M 580384	819
RE M 580384	707
RRE M 580384	756
M 580385	19926
M 580386	16355
M 580387	2985
M 580388	1891
M 580389	2104
M 580390	1019
STANDARD AU-R	485

BC 2K-3 SLUDGE

BC 2K-4 SLUDGE

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Standard Drilling PROJECT CARIBOO 2000 File # A000463R

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Au** gm/mt
M 580362	9.00
M 580371	9.70
M 580382	11.39
M 580385	21.41
M 580386	16.54
RE M 580386	17.05
STANDARD AU-1	3.38

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: SLUDGE PULP
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: FEB 23 2000 DATE REPORT MAILED: Feb28/00 SIGNED BY. D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Standard Drilling PROJECT CARIBOO 2000 File # A000587 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Au** ppb
B 169051	142
B 169052	25
B 169053	16
B 169054	<2
B 169055	28
B 169056	24
B 169057	35
B 169058	49
B 169059	85
B 169060	19
B 169061	41
B 169062	8
RE B 169062	9
RRE B 169062	13
B 169063	14
B 169064	17
B 169065	11
B 169066	24
B 169067	16
B 169068	4
B 169069	54
B 169070	328
B 169071	72
B 169072	25
B 169073	791
B 169074	679
RE B 169074	665
RRE B 169074	683
B 169075	97
B 169076	46
B 169077	40
B 169078	10
B 169079	320
B 169080	196
STANDARD AU-R	472

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: FEB 22 2000 DATE REPORT MAILED: Feb 29/00 SIGNED BY ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ~ FA ___

SAMPLE#	Au** ppb
B 169081	242
B 169082	233
B 169083	150
B 169084	31
B 169085	83
B 169086	1650
B 169087	2332
B 169088	188
RE B 169088	238
RRE B 169088	173
B 169089	2771
B 169090	1174
B 169091	820
B 169092	376
B 169093	680
STANDARD AU-R	464

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___/FA ____

ACME ALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST NCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(60 53-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Standard Drilling PROJECT CARIBOO 2000 File # A000680

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Au** ppb
B 169108	6290
B 169109	9596
B 169110	1160
B 169111	830
B 169112	2087
B 169113	1209
B 169114	1209
B 169115	5226
RE B 169115	5230
B 169116	884
B 169117	963
B 169118	727
STANDARD AU-R	451

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAR 2 2000 DATE REPORT MAILED: Mar 10/2000 SIGNED BY. J. Wang .D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All result[s] are considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Standard Drilling PROJECT CARIBOO 2000 File # A000680R

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm
B 169108	5	84	42	85	.8	197	85	1279	14.54	713	<8	3	2	71	<.2	3	<3	12	2.05	.074	2	19	.73	35	<.01	<3	.23	.02	.11	127
B 169109	6	40	37	64	1.3	213	118	1932	18.70	859	<8	7	2	100	.2	4	8	10	3.09	.137	2	14	1.01	26	<.01	<3	.25	.01	.15	42
B 169110	4	31	13	36	.3	124	32	1763	8.28	442	<8	<2	5	127	<.2	3	<3	8	3.39	.089	4	15	1.09	62	<.01	<3	.27	.01	.17	32
B 169111	5	84	11	45	<.3	91	35	805	8.08	353	<8	<2	3	53	<.2	<3	<3	6	1.27	.044	5	24	.54	55	<.01	<3	.24	.01	.15	81
B 169112	5	75	22	60	<.3	146	58	1002	11.66	671	<8	<2	3	56	<.2	<3	<3	6	1.37	.041	4	25	.51	50	<.01	<3	.23	.01	.15	107
B 169113	4	49	14	51	<.3	79	39	1712	8.44	320	<8	<2	5	103	.4	8	<3	7	2.77	.066	4	17	1.15	71	<.01	<3	.27	.02	.17	35
B 169114	3	92	20	100	.6	201	79	512	24.16	532	<8	<2	3	57	<.2	8	4	9	1.05	.138	2	13	.44	9	<.01	<3	.28	.01	.15	12
B 169115	4	123	40	116	1.2	276	157	512	27.30	1030	<8	3	2	70	<.2	<3	7	8	.92	.179	3	15	.34	9	<.01	<3	.27	.01	.16	13
RE B 169115	4	121	43	113	1.3	272	154	502	26.87	1011	<8	2	3	69	<.2	<3	8	9	.91	.178	2	16	.34	11	<.01	<3	.26	.01	.16	13
B 169116	7	155	15	141	<.3	186	155	615	19.90	825	<8	<2	2	61	<.2	3	6	11	.95	.190	4	16	.40	14	<.01	<3	.29	.01	.16	21
B 169117	6	213	23	199	.3	173	134	777	16.87	492	<8	<2	<2	50	.8	7	<3	12	.85	.201	5	21	.48	23	<.01	<3	.32	.01	.18	32
B 169118	3	188	9	73	.3	135	112	894	14.05	327	<8	<2	2	45	<.2	3	<3	12	.81	.193	4	14	.41	31	<.01	<3	.32	.01	.18	25
STANDARD C3	26	68	38	164	5.7	39	13	780	3.57	64	24	2	21	29	24.9	20	25	83	.58	.096	19	175	.61	154	.09	20	1.91	.04	.17	20
STANDARD G-2	2	3	4	41	<.3	8	4	536	2.04	2	<8	<2	4	69	<.2	<3	<3	42	.65	.101	7	77	.59	228	.13	<3	.93	.07	.48	2

GROUP 1D - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
- SAMPLE TYPE: SLUDGE PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAR 6 2000 **DATE REPORT MAILED:** Mar 10/2000 **SIGNED BY.** J. Wang .D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A000812 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Au** ppb	Au** oz/t
B 169119	9208	-
B 169120	99999	3.197
B 169121	5835	-
B 169122	2125	-
B 169123	595	-
B 169124	713	-
B 169125	535	-
B 169126	201	-
B 169127	273	-
B 169128	331	-
B 169129	278	-
B 169130	473	-
B 169131	355	-
B 169132	154	-
B 169133	301	-
B 169134	328	-
B 169135	108	-
B 169136	269	-
B 169137	822	-
B 169138	12204	-
B 169139	14141	-
B 169140	6349	-
RE B 169140	6062	-
B 169141	6232	-
B 169142	99999	3.714
B 169143	99999	4.984
B 169144	37735	-
B 169145	54456	-
B 169146	22786	-
B 169147	7916	-
B 169148	4807	-
B 169149	3033	-
B 169150	2357	-
B 169151	2150	-
B 169152	5154	-
STANDARD AU-R	466	-

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
AU** BY FIRE ASSAY FROM 1 A.T. SAMPLE.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAR 13 2000 DATE REPORT MAILED: March 22/2000 SIGNED BY. . . . . D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

SAMPLE#	Au** ppb	Au** ppb
B 169153	11603	-
B 169154	8202	-
B 169155	9850	-
B 169156	5271	-
B 169157	3671	-
B 169158	2847	-
B 169159	3028	-
B 169160	2581	-
B 169161	2838	-
B 169162	2796	-
B 169163	5868	-
B 169164	500	-
B 169165	3796	4311
RE B 169165	867	1053
B 169166	722	-
B 169167	379	-
B 169168	434	-
B 169169	4179	-
B 169170	542	-
B 169171	14042	-
B 169172	6929	-
B 169173	11261	-
B 169174	5778	-
B 169175	16076	-
B 169176	14327	-
B 169177	15066	-
B 169178	6611	-
B 169179	7205	-
B 169180	7042	-
B 169181	9472	-
B 169182	4723	-
B 169183	2249	-
B 169184	2913	-
B 169185	2347	-
B 169186	9123	-
STANDARD AU-R	472	-

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

SAMPLE#	Au** ppb
B 169187	8401
B 169188	4888
B 169189	4082
B 169190	2999
B 169191	1524
B 169192	3416
B 169193	3572
B 169194	5854
B 169195	11558
RE B 169195	8695
B 169196	5903
B 169197	3799
B 169198	5550
B 169199	2947
B 169200	1450
STANDARD AU-R	452

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All result[s] [are] considered the confidential property of the client. Acme assumes [its] liabilities for actual cost of the analysis only.

FA

852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716

(9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A000826 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Au** ppb
B 169201	516
B 169202	164
B 169203	1379
B 169204	335
B 169205	771
B 169206	435
B 169207	404
B 169208	481
B 169209	307
B 169210	551
RE B 169210	561
RRE B 169210	572
B 169211	655
B 169212	294
B 169213	1539
B 169214	8757
B 169215	3660
B 169216	448
B 169217	599
B 169218	480
B 169219	390
B 169220	337
B 169221	290
B 169222	200
RE B 169222	202
RRE B 169222	204
B 169223	228
B 169224	180
B 169225	334
B 169226	242
B 169227	259
B 169228	372
B 169229	413
B 169230	536
B 169231	418
STANDARD AU-R	457

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAR 14 2000 DATE REPORT MAILED: March 22/2000 SIGNED BY. C. Leong .D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All resul -e considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

SAMPLE#	Au** ppb
B 169232	445
B 169233	482
B 169234	302
B 169235	312
B 169236	321
RE B 169236	299
RRE B 169236	299
B 169237	453
B 169238	357
STANDARD AU-R	460

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All result e considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only. FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A000905 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: NED

SAMPLE#	Au** ppb
B 169239	449
B 169240	379
B 169241	255
B 169242	350
B 169243	192
B 169244	121
B 169245	84
RE B 169245	90
RRE B 169245	91
B 169246	32
B 169247	9
B 169248	<2
B 169249	11
B 169250	47
B 169251	43
B 169252	133
B 169253	335
B 169254	130
B 169255	980
B 169256	19
B 169257	19
B 169258	33
B 169259	61
B 169260	48
B 169261	2901
RE B 169261	2820
RRE B 169261	2830
B 169262	1316
B 169263	3104
B 169264	4507
B 169265	20884
B 169266	15785
B 169267	11447
B 169268	9197
B 169269	11966
STANDARD AU-R	472

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAR 21 2000 DATE REPORT MAILED: March 30/2000 SIGNED BY C. Leong D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

SAMPLE#	Au** ppb
B 169270	5721
B 169271	1692
B 169272	814
B 169273	781
B 169274	622
B 169275	1233
B 169276	647
B 169277	601
B 169278	724
B 169279	719
B 169280	958
B 169281	1017
B 169282	1084
B 169283	952
B 169284	998
RE B 169284	993
RRE B 169284	972
B 169285	2453
B 169286	2577
B 169287	1825
B 169288	1436
B 169289	1192
B 169290	1230
STANDARD AU-R	451

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Standard Drilling PROJECT CARIBOO GOLD 2000 File # A001054 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Au** ppb
B 169344	40
B 169345	278
B 169346	61
B 169347	55
B 169348	63
B 169349	67
B 169350	574
B 169351	454
B 169352	453
B 169353	134
RE B 169353	134
RRE B 169353	138
B 169354	288
B 169355	225
B 169356	228
B 169357	231
B 169358	320
B 169359	308
B 169360	143
B 169361	110
B 169362	102
B 169363	118
B 169364	129
B 169365	126
RE B 169365	121
RRE B 169365	167
B 169366	138
B 169367	181
B 169368	100
B 169369	346
B 169370	195
B 169371	223
B 169372	287
B 169373	144
B 169374	302
STANDARD AU-R	458

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: APR 4 2000 **DATE REPORT MAILED:** April 12/2000 **SIGNED BY** ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

SAMPLE#	Au** ppb
B 169375	1091
B 169376	489
B 169377	1593
B 169378	1837
B 169379	1029
B 169380	561
B 169381	765
B 169382	496
B 169383	1473
B 169384	652
B 169385	475
B 169386	277
RE B 169386	278
RRE B 169386	288
B 169387	195
B 169388	166
B 169389	126
B 169390	163
B 169391	139
B 169392	106
B 169393	94
B 169394	73
B 169395	76
STANDARD AU-R	473

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All result[illegible]e considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE (604) 253-3158 FAX (604) 253-1716

(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Standard Drilling PROJECT CARIBOO GOLD 2K File # A001128 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Au** ppb
B 169501	67
B 169502	16
B 169503	21
B 169504	585
B 169505	223
B 169506	231
B 169507	82
B 169508	111
B 169509	62
B 169510	36
RE B 169510	38
RRE B 169510	48
B 169511	26
B 169512	1596
B 169513	23612
B 169514	4175
B 169515	976
B 169516	294
B 169517	698
B 169518	732
B 169519	1020
B 169520	482
B 169521	331
B 169522	981
RE B 169522	1059
RRE B 169522	1106
B 169523	1007
B 169524	226
B 169525	184
B 169526	105
B 169527	107
B 169528	57
B 169529	66
B 169530	96
STANDARD AU-R	447

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: APR 11 2000 DATE REPORT MAILED: Apr 19/2000 SIGNED BY. D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

SAMPLE#	Au** ppb
B 169531	267
B 169532	82
B 169533	66
B 169534	106
B 169535	92
B 169536	79
B 169537	57
B 169538	45
B 169539	45
B 169540	55
B 169541	98
B 169542	64
B 169543	44
B 169544	34
B 169545	40
RE B 169545	39
RRE B 169545	181 ✓
B 169546	33
B 169547	30
B 169548	29
B 169549	39
B 169550	44
B 169551	38
B 169552	26
B 169553	36
STANDARD AU-R	455

Sample type: SLUDGE. Sampl beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All resul re considered the confidential property of th lient. Acme assumes liabilities for actual cost of the analysis only.

FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Standard Drilling PROJECT CARIBOO GOLD 2K File # A001188 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ned Reid

SAMPLE#	Au** ppb
B 169554	162
B 169555	97
B 169556	144
B 169557	75
B 169558	111
B 169559	247
B 169560	459
B 169561	82
B 169562	55
B 169563	61
B 169564	28
RE B 169564	26
RRE B 169564	26
B 169565	20
B 169566	42
B 169567	15
B 169568	28
B 169569	42
B 169570	51
B 169571	22
B 169572	20
B 169573	9
B 169574	18
B 169575	8
B 169576	24
RE B 169576	26
RRE B 169576	33
B 169577	23
B 169578	24
B 169579	45
B 169580	327
B 169581	444
B 169582	623
B 169583	193
STANDARD AU-R	490

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: APR 18 2000 DATE REPORT MAILED: April 26/2000 SIGNED BY. . . . . /.D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

D FA

SAMPLE#	Au** ppb
B 169584	29
B 169585	48
B 169586	62
B 169587	86
B 169588	21
B 169589	23
B 169590	47
B 169591	204
B 169592	43
B 169593	58
RE B 169593	127
RRE B 169593	57
B 169594	47
B 169595	36
B 169596	4465
B 169597	458
B 169598	135
B 169599	86
B 169600	88
B 169851	99
B 169852	46
B 169853	37
B 169854	13
RE B 169854	17
RRE B 169854	27
B 169855	9
B 169856	61
B 169857	38
B 169858	24
B 169859	234
STANDARD AU-R	488

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All result e considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) 1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Standard Drilling PROJECT Y2K CARIBOO GOLD File # A001292 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: R. Hall

SAMPLE#	Au** gm/mt
B 169396	<.01
B 169397	.03
B 169398	.01
B 169399	.04
B 169400	.07
B 169860	.10
B 169861	.32
B 169862	.49
B 169863	.28
B 169864	.37
B 169865	.14
RE B 169865	.14
RRE B 169865	.15
B 169866	.30
B 169867	.21
B 169868	.19
B 169869	.08
B 169870	.06
B 169871	.02
B 169872	.04
B 169873	.04
B 169874	.13
B 169875	.12
B 169876	.24
B 169877	.04
RE B 169877	.08
RRE B 169877	.03
B 169878	.02
B 169879	.06
B 169880	.04
B 169881	.04
B 169882	.04
B 169883	.02
B 169884	.03
STANDARD AU-1	3.39

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: SLUDGE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: APR 27 2000 DATE REPORT MAILED: May 3/2000 SIGNED BY. . . . . D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All resul re considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

SAMPLE#	Au** gm/mt
B 169885	.05
B 169886	.10
B 169887	.05
B 169888	.06
B 169889	.08
B 169890	.02
B 169891	.02
B 169892	.01
B 169893	.01
B 169894	.01
B 169895	.01
B 169896	<.01
B 169897	.04
B 169898	.02
B 169899	<.01
B 169900	.01
RE B 169900	<.01
RRE B 169900	<.01
B 170851	.14
B 170852	.18
B 170853	.17
B 170854	.03
B 170855	.01
B 170856	.03
B 170857	.02
B 170858	.04
STANDARD AU-1	3.28

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All resul re considered the confidential property of the client. Acme assumes liabilities for actual cost of the analysis only.

FA

604 253 1716 TO 12509943338

(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD File # A001567 Page 1

302 - 1455 Granville St., Vancouver BC V6Z 1T1 Submitted by: K. Ross

BC2K-18 sludge

SAMPLE#	Au** gm/mt
B 170859	.02
B 170860	.04
B 170861	.02
B 170862	.02
B 170863	.43
B 170864	.12
B 170865	.10
B 170866	.22
B 170867	2.83
B 170868	3.83
B 170869	6.04
B 170870	1.31
RE B 170870	2.35
RRE B 170870	1.14
B 170871	.25
B 170872	.27
B 170873	.32
B 170874	.43
B 170875	.44
B 170876	.97
B 170877	.18
B 170878	.08
B 170879	.15
B 170880	.09
B 170881	.07
B 170882	.14
RE B 170882	.16
RRE B 170882	.75 *
B 170883	.05
B 170884	.06
B 170885	.07
B 170886	.06
B 170887	.04
B 170888	.05
STANDARD AU-1	3.63

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: SLUDGE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAY 23 2000 DATE REPORT MAILED: May 30/2000 SIGNED BY: C. [illegible] D. TOYE, C. LEONG, J. WANG: CERTIFIED B.C. ASSAYERS

* Subject to reassay check

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Au** gm/mt
B 170889	.09
B 170890	.36
B 170891	.24
B 170892	.32
B 170893	.19
B 170894	.97
B 170895	1.35
B 170896	1.05
B 170897	.91
B 170898	.67
B 170899	.48
B 170900	1.61
RE B 170900	2.12
RRE B 170900	1.64
B 170901	.51
B 170902	.37
B 170903	.43
B 170904	.11
B 170905	.11
B 170906	.08
B 170907	2.99
B 170908	.22
B 170909	2.27
B 170910	1.05
B 170911	.28
B 170912	.85
RE B 170912	.70
RRE B 170912	.80
B 170913	.93
B 170914	.69
B 170915	.90
B 170916	.43
B 170917	.57
B 170918	.40
B 170919	.61
STANDARD AU-1	3.61

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data k FA f

MAY 30'00 17:16 FR ACME LABS 604 253 1716 TO 12509943338 P.03/06

SAMPLE#	Au** gm/mt
B 170920	1.61
B 170921	.52
B 170922	.45
B 170923	.66
B 170924	.45
B 170925	.40
B 170926	.56
B 170927	.35
B 170928	.24
B 170929	.19
B 170930	.16
RE B 170930	.18
RRE B 170930	.17
B 170931	.19
B 170932	.37
B 170933	.29
B 170934	.37
STANDARD AU-1	3.66

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Date FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Standard Drilling PROJECT CARIBOO GOLD File # A001627 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ken Lord

BC2K-19 Sludge

SAMPLE#	Au** gm/mt
B 170935	.03
B 170936	1.05
B 170937	1.01
B 170938	.31
B 170939	3.60
B 170940	1.57
B 170941	.38
B 170942	.55
B 170943	.31
B 170944	.32
B 170945	.30
RE B 170945	.31
RRE B 170945	.33
B 170946	.35
B 170947	.14
B 170948	.17
B 170949	.26
B 170950	.11
B 170951	.58
B 170952	.58
B 170953	.19
B 170954	.22
B 170955	.91
B 170956	34.73
B 170957	45.55
RE B 170957	45.14
RRE B 170957	46.52
B 170958	23.77
B 170959	24.72
B 170960	26.96
B 170961	22.88
B 170962	30.14
B 170963	14.36
B 170964	12.44
STANDARD AU-1	3.70

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: SLUDGE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: MAY 29 2000 DATE REPORT MAILED: June 1/00 SIGNED BY ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Date 6 FA

SAMPLE#	Au** gm/mt
B 170965	6.18
B 170966	9.48
B 170967	9.42
B 170968	10.44
B 170969	9.87
B 170970	10.89
B 170971	9.02
B 170972	7.07
B 170973	5.88
B 170974	6.73
RE B 170974	6.60
RRE B 170974	6.55
B 170975	6.80
B 170976	12.51
B 170977	9.61
B 170978	9.25
B 170979	8.73
STANDARD AU-1	3.64

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

International Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A001762 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** ppb
B 170401	462
B 170402	2451
B 170403	1147
B 170404	359
B 170405	3990
B 170406	477
B 170407	205
B 170408	234
B 170409	446
B 170410	370
RE B 170410	373
RRE B 170410	357
B 170411	570
B 170412	177
B 170413	456
B 170414	493
B 170415	449
B 170416	533
B 170417	859
B 170418	855
B 170419	283
B 170420	301
B 170421	467
B 170422	403
B 170423	590
B 170424	491
RE B 170424	453
RRE B 170424	444
B 170425	258
B 170426	315
B 170427	242
B 170428	275
B 170429	176
B 170980	594
B 170981	589
STANDARD AU-R	472

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUN 8 2000 DATE REPORT MAILED: June 16/00 SIGNED BY..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

International Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A001762 Page 2

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** ppb	Au2 ppb
B 170982	202	-
B 170983	513	-
B 170984	1881	-
B 170985	1214	-
B 170986	3902	-
B 170987	1040	-
B 170988	92	-
B 170989	139	-
B 170990	38	-
B 170991	250	-
B 170992	240	114
RE B 170992	111	128
RRE B 170992	111	327
B 170993	194	-
B 170994	231	-
B 170995	162	-
B 170996	209	-
B 170997	265	-
B 170998	970	-
B 170999	57	-
B 171000	3025	-
STANDARD AU-R	474	-

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
AU2 - 2nd ANALYSIS BY FA/ICP.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUN 8 2000 DATE REPORT MAILED: Jun 16/00 SIGNED BY. C. Leong .D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data___ FA ___

ACME ALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST NCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(6 53-1716
(9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

International Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A001793

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** ppb
B 170430	611
B 170431	155
B 170432	520
B 170433	1318
B 170434	764
B 170435	748
B 170436	299
B 170437	75
B 170438	73
B 170439	200
B 170440	420
RE B 170440	325
RRE B 170440	222
B 170441	100
B 170442	257
B 170443	162
B 170444	66
B 170445	126
B 170446	141
B 170447	102
B 170448	53
B 170449	50
B 170450	79
B 170451	131
B 170452	89
RE B 170452	95
RRE B 170452	89
B 170453	603
B 170454	310
B 170455	164
B 170456	61
B 170457	110
B 170458	108
B 170459	18
STANDARD AU-R	479

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUN 12 2000 DATE REPORT MAILED: Jun 20/00 SIGNED BY ..D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME LYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. NCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(60 53-1716
(9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD 2000 File # A001872 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** ppb	Au** * ppb
B 170460	354	86
B 170461	1801	800
B 170462	3974	748
B 170463	1516	1440
B 170464	2331	2250
B 170465	1114	1132
B 170466	244	-
B 170467	350	-
B 170468	273	-
B 170469	259	-
B 170470	84	-
RE B 170470	83	-
RRE B 170470	78	-
B 170471	126	-
B 170472	118	-
B 170473	85	-
B 170474	57	-
B 170475	61	-
B 170476	37	-
B 170477	52	-
B 170478	373	-
B 170479	112	-
B 170480	128	-
B 170481	51	-
B 170482	661	68
RE B 170482	69	68
RRE B 170482	75	-
B 170483	23	-
B 170484	19	-
B 170485	23	-
B 170486	36	-
B 170487	97	-
B 170488	33	-
B 170489	30	-
STANDARD AU-R	476	-

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUN 16 2000 DATE REPORT MAILED: Jun 26/00 SIGNED BY. ..D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

* Duplicate gold reassay

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA

SAMPLE#	Au** ppb
B 170490	105
B 170491	95
B 170492	42
B 170493	178
B 170494	362
B 170495	70
B 170496	118
RE B 170496	123

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data__ FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. File # A002067 Page 1
305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** ppb
B 170601	490
B 170602	5423
B 170603	2574
B 170604	1036
B 170605	223
B 170606	584
B 170607	609
B 170608	238
B 170609	1619
B 170610	382
RE B 170610	377
RRE B 170610	400
B 170611	521
B 170612	274
B 170613	270
B 170614	195
B 170615	129
B 170616	108
B 170617	142
B 170618	219
B 170619	112
B 170620	116
B 170621	274
B 170622	393
RE B 170622	387
RRE B 170622	362
B 170623	223
B 170624	267
B 170625	207
B 170626	343
B 170627	258
B 170628	314
B 170629	276
B 170630	189
STANDARD AU-R	472

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUN 28 2000 DATE REPORT MAILED: July 12/00 SIGNED BY. C. Leong .D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data A FA

SAMPLE#	Au** ppb
B 170631	217
B 170632	151
B 170633	83
B 170634	114
B 170635	73
RE B 170635	66
STANDARD AU-R	472

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD 2000 File # A002068

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Lord

SAMPLE#	Au** ppb
B 170636	3482
B 170637	10703
B 170638	5729
B 170639	1046
B 170640	1828
B 170641	559
B 170642	3263
B 170643	184
B 170644	697
B 170645	303
RE B 170645	311
RRE B 170645	288
B 170646	39
B 170647	3312
B 170648	2160
B 170649	677
B 170650	9328
B 170651	1634
B 170652	8310
B 170653	4070
B 170654	965
B 170655	747
B 170656	1294
B 170657	5196
RE B 170657	5012
RRE B 170657	5121
B 170658	12462
B 170659	6004
B 170660	763
B 170661	578
B 170662	114
STANDARD AU-R	475

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUN 28 2000 DATE REPORT MAILED: July 7/00 SIGNED BY ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data 1 FA 1

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD 2000 File # A002124

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ken Lord

SAMPLE#	Au** ppb
B 170663	1112
B 170664	683
B 170665	2011
B 170666	298
B 170667	188
B 170668	204
B 170669	1706
B 170670	339
B 170671	180
B 170672	57
RE B 170672	73
RRE B 170672	105
B 170673	68
B 170674	192
B 170675	418
B 170676	212
B 170677	141
B 170678	269
B 170679	1595
B 170680	563
B 170681	1206
B 170682	1605
RE B 170682	1556
RRE B 170682	1644
B 170683	421
B 170684	3044
B 170685	449
B 170686	350
B 170687	306
STANDARD AU-R	484

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUL 4 2000 DATE REPORT MAILED: July 12/00 SIGNED BY. ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD 2000 File # A002168

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** ppb
B 170688	237
B 170689	335
B 170690	323
B 170691	4398
B 170692	4017
B 170693	1887
B 170694	600
B 170695	2988
B 170696	5109
B 170697	3379
B 170698	1171
RE B 170698	1279
RRE B 170698	1103
B 170700	698
B 170701	238
B 170702	318
B 170703	1007
B 170704	1013
B 170705	6834
B 170706	5137
B 170707	1127
B 170708	521
B 170709	3121
B 170710	557
B 170711	1366
B 170712	211
RE B 170712	235
RRE B 170712	211
B 170713	707
B 170714	414
B 170715	236
B 170716	345
B 170717	829
B 170718	839
STANDARD AU-R	470

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUN 6 2000 DATE REPORT MAILED: July 12/00 SIGNED BY .....D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002328 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: R. Hall

SAMPLE#	Au** ppb
B 170719	102
B 170720	136
B 170721	518
B 170722	652
B 170723	6763
B 170724	1627
B 170725	1293
B 170726	575
B 170727	4072
B 170728	1268
B 170729	4666
B 170730	969
RE B 170730	1026
RRE B 170730	1043
B 170731	1124
B 170732	586
B 170733	191
B 170734	456
B 170735	146
B 170736	751
B 170737	2032
B 170738	9360
B 170739	4085
B 170740	7758
B 170741	3158
B 170742	2757
RE B 170742	2791
RRE B 170742	2829
B 170743	1486
B 170744	19235
B 170745	8383
B 170746	3231
B 170747	2567
B 170748	1294
STANDARD AU-R	480

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUL 13 2000 DATE REPORT MAILED: July 21/00 SIGNED BY: ..... D. TOYE, C. LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** ppb
B 170749	4420
B 170750	3530
B 170751	1065
B 170752	984
B 170753	850
B 170754	523
B 170755	474
RE B 170755	410
RRE B 170755	426
B 170756	518
B 170757	1046
STANDARD AU-R	457

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Date FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002439 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: R. Hall

SAMPLE#	Au** ppb
B 170758	230
B 170759	176
B 170760	416
B 170761	349
B 170762	237
B 170763	323
B 170764	6225
B 170765	1039
B 170766	665
B 170767	1617
B 170768	3474
RE B 170768	3561
RRE B 170768	3205
B 170769	1656
B 170770	538
B 170771	241
B 170772	719
B 170773	268
B 170774	140
B 170775	306
B 170776	346
B 170777	15
B 170778	25
B 170779	363
B 170780	1047
RE B 170780	985
RRE B 170780	1048
B 170781	9905
B 170782	3660
B 170783	898
B 170784	1174
B 170785	1025
B 170786	2579
B 170787	377
STANDARD AU-R	466

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUL 19 2000 DATE REPORT MAILED: July 28/00 SIGNED BY: C. T. D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** ppb
B 170788	173
B 170789	158
B 170790	51
B 170791	845
B 170792	350
B 170793	80
B 170794	60
B 170795	145
B 170796	137
B 170797	127
B 170798	781
RE B 170798	800
RRE B 170798	826
B 170799	174
B 170800	146
B 170801	170
B 170802	333
B 170803	157
STANDARD AU-R	481

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002590 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: R. Hall

SAMPLE#	Au** ppb
B 170804	79
B 170805	81
B 170806	37
B 170807	275
B 170808	380
B 170809	234
B 170810	446
B 170811	1093
B 170812	286
B 170813	44
B 170814	74
RE B 170814	199
RRE B 170814	167
B 170815	72
B 170816	80
B 170817	113
B 170818	962
B 170819	6216
B 170820	22725
B 170821	16770
B 170822	22240
B 170823	11155
B 170824	70575
B 170825	36269
B 170826	8503
RE B 170826	8511
RRE B 170826	9169
B 170827	8077
B 170828	1641
B 170829	2196
B 170830	944
B 170831	2544
B 170832	1328
B 170833	1777
STANDARD AU-R	485

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUL 26 2000 DATE REPORT MAILED: Aug 2/00 SIGNED BY. . . . . D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** ppb
B 170834	1826
B 170835	1853
B 170836	521
B 170837	501
B 170838	680
B 170839	866
B 170840	387
B 170841	703
B 170842	488
B 170843	270
B 170844	345
RE B 170844	357
RRE B 170844	331
B 170845	1664
B 170846	997
B 170847	598
B 170848	1414
B 170849	767
B 170850	674
B 172101	43
B 172102	114
B 172103	45
B 172104	111
B 172105	44
B 172106	17
RE B 172106	23
RRE B 172106	22
B 172107	8
B 172108	45
B 172109	31
B 172110	319
B 172111	225
B 172112	177
B 172113	14909
B 172114	6898
STANDARD AU-R	478

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

DATE FA

SAMPLE#	Au** ppb
B 172115	7249
B 172116	17458
B 172117	11743
B 172118	2483
B 172119	1013
B 172120	2362
B 172121	465
B 172122	933
B 172123	1272
B 172124	1766
RE B 172124	1756
RRE B 172124	1731
B 172125	1657
B 172126	3069
B 172127	10276
B 172128	6693
B 172129	12748
B 172130	12560
B 172131	23821
B 172132	4220
B 172133	4704
B 172134	938
B 172135	366
B 172136	1842
RE B 172136	1818
RRE B 172136	1984
B 172137	945
B 172138	549
B 172139	462
B 172140	296
B 172141	550
STANDARD AU-R	467

Sample type: SLUDGE. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME LYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. NCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(60 53-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002712 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: R. Hall

SAMPLE#	Au** ppb
B 172142	49
B 172143	44
B 172144	209
B 172145	92
B 172146	27
B 172147	46
B 172148	20
B 172149	380
B 172150	26
B 172151	20
B 172152	15
RE B 172152	14
RRE B 172152	15
B 172153	40
B 172154	26
B 172155	80
B 172156	72
B 172157	160
B 172158	1925
B 172159	2003
B 172160	26897
B 172161	17835
B 172162	27090
B 172163	11568
B 172164	26977
RE B 172164	27293
RRE B 172164	27880
B 172165	20880
B 172166	7350
B 172167	2897
B 172168	1252
B 172169	715
B 172170	1336
B 172171	1330
STANDARD AU-R	483

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE R150 Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: AUG 1 2000 DATE REPORT MAILED: Aug 9/00 SIGNED BY: C.T. .D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

Assay recommended for gold > 1000 ppb

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data FA

SAMPLE#	Au** ppb
B 172172	3363
B 172173	4332
B 172174	1124
B 172175	487
B 172176	415
B 172177	810
B 172178	308
B 172179	249
B 172180	1203
B 172181	577
B 172182	211
B 172183	160
B 172184	934
RE B 172184	943
RRE B 172184	968
B 172185	391
B 172186	395
B 172187	275
B 172188	386
B 172189	285
B 172190	249
STANDARD AU-R	474

Sample type: SLUDGE R150. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. NCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(60 '53-1716
(O 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003017 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au* ppb
B 171101	11.2
B 171102	3.2
B 171103	40.6
B 171104	436.2
B 171105	290.3
B 171106	192.5
B 171107	940.5
B 171108	8558.3
B 171109	9644.9
B 171110	3349.5
RE B 171110	2785.9
RRE B 171110	2539.4
B 171111	690.0
B 171112	321.7
B 171113	259.3
B 171114	270.4
B 171115	4770.9
B 171116	13294.2
B 171117	10419.7
B 171118	14620.7
B 171119	50018.5
B 171120	49865.5
B 171121	28587.3
B 171122	30554.6
RE B 171122	29275.8
RRE B 171122	30249.8
B 171123	25683.9
B 171124	12959.0
B 171125	26417.6
B 171126	19498.2
B 171127	17672.1
B 171128	14686.4
B 171129	17195.6
STANDARD DS2	190.0

AU* BY ACID LEACHED, ANALYZE BY ICP-MS (10 gm).
- SAMPLE TYPE: SLUDGE R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: AUG 15 2000 DATE REPORT MAILED: Aug 30/00 SIGNED BY. C. Leong .D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

Assay gold recommended for >1000 ppb

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Date FA

SAMPLE#	Au* ppb
B 171130	43837.8
B 171131	14267.2
B 171132	22129.1
B 171133	16736.5
B 171134	21085.7
B 171135	11963.2
B 171136	17349.9
B 171137	10048.8
B 171138	13993.5
B 171139	16660.2
RE B 171139	16100.7
STANDARD DS2	220.4

Sample type: SLUDGE R150 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003018 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** ppb
B 171051	21
B 171052	3944
B 171053	271
B 171054	118
B 171055	4
B 171056	7
B 171057	13
B 171058	7
B 171059	7
B 171060	13
RE B 171060	9
RRE B 171060	15
B 171061	12
B 171062	9
B 171063	9
B 171064	42
B 171065	6919
B 171066	1357
B 171067	3535
B 171068	14440
B 171069	19271
B 171070	4467
B 171071	903
B 171072	1105
RE B 171072	1104
RRE B 171072	1061
B 171073	639
B 171074	540
B 171075	562
B 171076	817
B 171077	528
B 171078	700
B 171079	538
B 171080	497
STANDARD AU-R	484

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE R150 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: AUG 15 2000 DATE REPORT MAILED: Aug 25/00 SIGNED BY: ..... D. YOVE, C. LEONG, J. WANG: CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** ppb
B 171081	459
B 171082	548
B 171083	1193
B 171084	1961
B 171085	1374
B 171086	1851
B 171087	1027
B 171088	839
B 171089	809
B 171090	1061
RE B 171090	1036
RRE B 171090	984
B 171091	1347
B 171092	675
B 171093	311
B 171094	402
B 171095	319
B 171096	841
B 171097	395
B 171098	753
B 171099	354
B 171100	297
B 171140	210
B 171141	203
B 171142	28655
RE B 171142	28870
RRE B 171142	28652
B 171143	10663
B 171144	2558
B 171145	1650
B 171146	1145
B 171147	581
B 171148	477
B 171149	359
B 171150	622
STANDARD AU-R	466

Sample type: SLUDGE R150 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA

SAMPLE#	Au** ppb
B 172191	835
B 172192	697
B 172193	890
B 172194	410
RE B 172194	503

Sample type: SLUDGE R150 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. File # A003396
305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** ppb
B 171551	6
B 171552	23
B 171553	7
B 171554	19
B 171555	49
B 171556	149
B 171557	97
B 171558	21
B 171559	191
B 171560	306
RE B 171560	310
RRE B 171560	425
B 171561	207
B 171562	90
B 171563	180
B 171564	139
B 171565	75
B 171566	64
B 171567	76
B 171568	85
B 171569	212
B 171570	170
B 171571	133
B 171572	131
B 171573	168
RE B 171573	178
RRE B 171573	172
B 172195	32
B 172196	595
B 172197	69
B 172198	62
B 172199	7
B 172200	<2
STANDARD AU-R	486

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE R150 Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: SEP 6 2000 DATE REPORT MAILED: Sept 15/00 SIGNED BY. C. Leong D. TOYE, C.LEONG. J. WANG: CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

... Accredited Co.)
... VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(...4)253-1716

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. File # A003474
305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** ppb
B 171574	142
B 171575	135
B 171576	87
B 171577	69
B 171578	52
B 171579	51
B 171580	50
B 171581	33
B 171582	59
B 171583	36
B 171584	34
RE B 171584	32
RRE B 171584	35
B 171585	43
B 171586	42
B 171587	60
B 171588	46
B 171589	27
B 171590	49
B 171591	45
B 171592	66
B 171593	41
B 171594	56
B 171595	56
B 171596	34
RE B 171596	28
RRE B 171596	31
B 171597	170
B 171598	1218
B 171599	394
B 171600	345
B 171601	55
B 171602	159
B 171603	119
STANDARD AU-R	473

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE R150 Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: SEP 11 2000 DATE REPORT MAILED: Sept 19/00 SIGNED BY: ... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data A FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003625 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** ppb
B 171604	244
B 171605	192
B 171606	82
B 171607	123
B 171608	158
B 171609	153
B 171610	169
B 171611	94
B 171612	71
B 171613	144
B 171614	101
RE B 171614	97
RRE B 171614	96
B 171615	85
B 171616	53
B 171617	54
B 171618	81
B 171619	45
B 171620	63
B 171621	35
B 171622	30
B 171623	51
B 171624	101
B 171625	75
B 171626	133
RE B 171626	114
RRE B 171626	124
B 171627	87
B 171628	58
B 171629	257
B 171630	136
B 171631	358
B 171632	273
B 171633	226
STANDARD AU-R	499

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SLUDGE R150 Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: SEP 18 2000 DATE REPORT MAILED: Sept 25/00 SIGNED BY: ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data FA

SAMPLE#	Au** ppb
B 171634	332
B 171635	178
B 171636	203
B 171637	176
B 171638	299
B 171639	254
B 171640	156
RE B 171640	191
RRE B 171640	140
B 171641	195
B 171642	53
B 171643	227
STANDARD AU-R	489

Sample type: SLUDGE R150. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ___

APPENDIX IX

ASSAY CERTIFICATES

PART 4 - SOIL SAMPLE ASSAY CERTIFICATES

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002440 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** ppb
B 171401	59
B 171402	39
B 171403	223
B 171404	72
B 171405	114
B 171406	84
B 171407	34
B 171408	58
B 171409	51
B 171410	27
B 171411	25
B 171412	15
B 171413	885
B 171414	151
B 171415	150
RE B 171426	48
B 171416	148
B 171417	323
B 171418	494
B 171419	247
B 171420	88
B 171421	4998
B 171422	97
B 171423	111
B 171424	270
B 171425	39
B 171426	35
B 171427	103
B 171428	30
B 171429	113
B 171430	69
B 171431	60
B 171432	60
B 171433	83
B 171434	114
STANDARD AU-S	52

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SOIL Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUL 19 2000 DATE REPORT MAILED: July 28/00 SIGNED BY. C. Leong .D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data A FA

SAMPLE#	Au** ppb
B 171435	55
B 171436	61
B 171437	114
B 171438	132
B 171439	119
B 171440	105
B 171441	100
B 171442	155
B 171443	99
B 171444	70
B 171445	69
B 171446	208
B 171447	104
B 171448	65
B 171449	52
B 171450	112
RE B 171455	205
B 171451	54
B 171452	42
B 171453	91
B 171454	159
B 171455	185
B 171456	97
B 171457	56
B 171458	121
B 171459	60
B 171460	386
B 171461	34
B 171462	70
B 171463	78
B 171464	68
B 171465	30
B 171466	42
B 171467	57
B 171468	31
STANDARD AU-S	49

Sample type: SOIL. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data K FA

SAMPLE#	Au** ppb
B 171469	15
B 171470	62
B 171471	75
B 171472	123
B 171473	110
B 171474	198
B 171475	133
B 171476	328
B 171477	149
B 171478	149
B 171479	105
B 171480	68
B 171481	171
B 171482	82
B 171483	85
B 171484	97
B 171485	192
RE B 171473	105
B 171486	91
B 171487	91
B 171488	42
B 171489	43
B 171490	1161
B 171491	145
B 171492	624
B 171493	61
B 171494	81
B 171495	60
B 171496	75
B 171497	71
B 171498	128
B 171499	124
B 171500	495
B 171501	133
B 171502	478
STANDARD AU-S	46

Sample type: SOIL. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Date FA

SAMPLE#	Au** ppb
B 171503	207
B 171504	75
B 171505	63
B 171506	76
B 171507	50
B 171508	24
B 171509	24
B 171510	14
B 171511	100
B 171512	40
RE B 171513	48
B 171513	45
B 171514	46
B 171515	163
B 171516	137
B 171517	95
B 171518	32
STANDARD AU-S	47

Sample type: SOIL. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002440R Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 171401	.5	44	28	72	.5	34	15	893	4.01	42	2	<2	4	16	.3	<.5	.5	35	.22	.081	29	31	.42	131	.012	3	1.49	.005	.10	2	<1	3.0	2	.02	4
B 171402	.4	34	26	63	.4	30	15	797	3.68	40	2	<2	4	14	.3	.5	<.5	35	.19	.063	30	29	.41	106	.014	3	1.30	.003	.09	2	<1	2.6	2	.01	3
B 171403	.4	40	28	77	.4	38	19	955	4.38	43	2	<2	3	18	.4	.7	.5	44	.23	.090	28	38	.52	140	.014	3	1.67	.004	.13	2	<1	3.1	1	.02	5
B 171404	.6	41	29	79	.2	34	17	919	4.12	44	2	<2	5	14	.3	<.5	.7	38	.16	.061	30	33	.44	128	.015	3	1.49	.002	.09	2	<1	2.8	2	.01	4
B 171405	.3	40	45	72	.4	35	18	1204	4.13	51	2	<2	3	17	.4	<.5	1.1	36	.25	.085	27	28	.36	126	.015	3	1.32	.003	.10	2	<1	2.3	1	.02	3
B 171406	.8	32	24	61	.1	31	12	449	5.19	62	1	<2	5	9	.3	.8	1.4	34	.10	.082	27	19	.17	79	.010	1	.99	.001	.05	3	<1	1.5	2	.02	4
B 171407	.4	57	17	75	.2	76	19	669	5.52	155	1	<2	3	10	.8	<.5	1.2	31	.03	.063	21	21	.14	53	.009	<1	.97	.001	.05	4	<1	2.3	2	.02	2
B 171408	.3	19	21	61	.1	17	7	391	4.63	39	1	<2	5	5	.4	<.5	.5	37	.05	.110	25	21	.18	62	.014	1	1.09	<.001	.05	4	<1	1.4	2	.01	4
B 171409	.7	18	17	48	.1	17	7	456	2.81	38	1	<2	4	6	.2	<.5	.5	24	.04	.057	28	15	.17	65	.006	1	.87	<.001	.04	2	<1	1.0	2	.01	2
B 171410	.8	23	17	54	.2	22	13	470	3.17	44	1	<2	3	16	.2	<.5	1.1	29	.11	.064	28	14	.14	103	.007	1	.86	.001	.05	1	<1	1.0	1	.01	3
B 171411	.7	17	11	28	.4	12	5	208	1.59	19	1	<2	1	15	.2	.6	<.5	16	.17	.059	24	8	.08	62	.005	<1	.62	.001	.04	1	<1	.6	<1	.02	2
B 171412	.5	20	8	29	.1	14	3	88	1.37	19	<1	<2	2	8	<.2	<.5	<.5	17	.04	.040	36	6	.03	31	.006	3	.35	<.001	.03	1	<1	.6	<1	<.01	2
B 171413	1.2	51	39	85	.4	35	12	421	5.54	119	3	<2	3	72	.5	.9	1.7	32	.20	.191	25	22	.21	117	.008	1	1.07	.004	.09	2	<1	1.4	2	.04	3
B 171414	1.6	44	41	61	.5	35	9	305	3.45	97	2	<2	2	35	.4	4.5	9.1	23	.08	.098	28	13	.08	80	.005	<1	.75	.001	.06	1	<1	1.2	1	.02	2
B 171415	.4	26	21	57	.7	19	7	310	2.98	34	1	<2	2	12	.3	.5	1.5	33	.12	.080	23	24	.25	185	.007	<1	1.44	.004	.13	3	<1	1.7	<1	.02	4
RE B 171415	.4	26	21	58	.7	20	7	318	3.02	34	2	<2	2	12	.3	<.5	1.1	35	.12	.082	24	24	.25	189	.007	1	1.47	.004	.13	2	<1	1.8	1	.02	4
B 171416	.4	16	14	49	.1	19	7	253	2.56	29	1	<2	4	8	<.2	.5	.6	23	.10	.045	30	20	.33	91	.009	<1	1.02	.001	.07	2	<1	1.5	<1	<.01	2
B 171417	.4	30	28	64	.7	29	15	698	4.13	62	1	<2	4	12	.3	<.5	1.8	27	.16	.065	28	21	.29	81	.014	1	1.02	.001	.06	3	<1	1.9	1	.01	2
B 171418	.6	20	20	50	.3	22	10	431	3.40	51	1	<2	3	11	.3	<.5	1.5	27	.16	.059	27	21	.30	68	.013	<1	.98	.001	.05	4	<1	1.5	1	.01	2
B 171419	.4	20	17	50	.5	20	11	513	3.03	41	1	<2	3	12	.2	<.5	.8	29	.14	.048	28	20	.31	93	.008	<1	1.07	<.001	.06	2	<1	1.6	<1	.01	2
B 171420	.4	42	34	73	.9	34	15	1333	4.33	49	2	<2	3	22	.5	<.5	1.3	33	.27	.123	21	27	.33	194	.008	1	1.51	.007	.13	2	<1	2.8	1	.03	3
B 171421	.9	33	157	62	1.2	28	14	869	4.36	522	2	3	6	16	.5	1.8	8.3	14	.22	.063	20	14	.27	60	.004	1	.65	<.001	.04	5	<1	2.0	1	.23	<1
B 171422	.2	41	31	67	1.3	30	17	952	3.93	46	2	<2	4	15	.5	.5	1.2	32	.18	.067	26	27	.35	121	.010	2	1.31	.001	.09	2	<1	2.5	3	.01	2
B 171423	.8	46	35	72	1.0	37	16	1300	4.11	61	3	<2	2	22	.5	.7	1.6	33	.27	.104	23	24	.32	169	.008	<1	1.37	.002	.10	3	<1	2.4	2	.04	2
B 171424	.3	26	23	51	.3	26	13	511	3.27	43	1	<2	4	9	.2	<.5	1.1	26	.11	.052	30	23	.37	81	.008	1	1.07	<.001	.06	2	<1	2.0	<1	.01	2
B 171425	.3	41	28	62	.5	25	8	292	3.75	40	1	<2	3	10	.4	<.5	1.6	38	.13	.046	27	26	.28	124	.011	<1	1.33	.002	.08	2	<1	2.0	1	.01	3
B 171426	<.2	22	22	58	.1	26	10	376	3.60	41	1	<2	9	7	.2	<.5	.6	29	.10	.038	33	24	.38	88	.013	1	1.18	.001	.07	2	<1	2.1	<1	<.01	2
B 171427	.2	17	16	49	.1	21	8	278	3.03	31	1	<2	3	9	<.2	<.5	<.5	31	.16	.039	29	22	.37	99	.015	<1	1.02	<.001	.05	2	<1	1.4	<1	<.01	2
B 171428	.2	25	21	57	.1	26	11	418	3.47	35	1	<2	4	10	<.2	<.5	<.5	29	.16	.046	28	24	.36	90	.009	<1	1.13	<.001	.07	2	<1	1.9	1	<.01	2
B 171429	.2	33	33	58	.3	28	11	410	3.29	48	2	<2	7	15	<.2	.6	1.4	21	.19	.061	36	16	.31	77	.009	1	.91	<.001	.05	2	<1	2.4	<1	.01	1
B 171430	.3	49	27	76	.8	40	16	1298	4.12	45	4	<2	3	26	.5	<.5	1.3	31	.38	.107	25	28	.42	175	.009	1	1.56	.005	.11	2	<1	3.5	1	.03	2
B 171431	<.2	36	26	73	.5	34	16	873	4.02	46	2	<2	4	14	.5	<.5	.7	34	.19	.079	26	28	.42	141	.009	1	1.51	.003	.09	3	<1	3.0	1	.02	2
B 171432	<.2	34	23	63	.5	34	14	699	3.59	44	2	<2	4	15	.3	<.5	.6	29	.23	.067	29	25	.42	105	.013	1	1.27	.002	.07	2	<1	3.2	<1	.01	1
B 171433	<.2	31	25	54	.3	30	12	507	3.34	46	2	<2	5	14	.3	<.5	1.0	22	.20	.062	33	19	.35	87	.008	<1	1.07	.001	.06	2	<1	2.6	1	.01	1
B 171434	.2	34	28	69	.7	32	17	734	4.01	45	2	<2	3	13	.4	<.5	.9	29	.17	.074	27	23	.34	103	.010	<1	1.27	.003	.08	2	<1	2.1	2	.01	1
STANDARD C3	25.2	70	34	164	5.5	34	11	789	3.20	57	23	<2	21	28	24.5	16.0	22.4	80	.57	.093	20	165	.60	153	.085	23	1.78	.039	.16	16	1	4.4	1	.03	5
STANDARD G-2	1.3	3	3	42	<.1	9	3	542	1.98	<1	4	<2	5	68	<.2	<.5	<.5	41	.63	.099	9	76	.59	227	.129	2	.94	.073	.47	3	<1	2.5	<1	<.01	4

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2:2:2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
- SAMPLE TYPE: SOIL PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: NOV 23 2000 DATE REPORT MAILED: Nov 28/00 SIGNED BY: ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 171435	<.2	32	27	72	.4	27	14	654	4.41	41	2	<2	4	9	.6	<.5	.9	34	.12	.081	26	25	.31	113	.015	<1	1.39	.003	.07	2	<1	2.2	1	.01	4
B 171436	<.2	35	25	59	<.1	32	14	580	3.62	48	1	<2	10	6	.3	.6	.9	21	.06	.025	37	19	.37	54	.011	<1	1.02	.002	.06	2	<1	2.2	2	<.01	2
B 171437	.3	27	25	48	.1	21	8	252	3.70	54	1	<2	3	5	.3	<.5	2.1	24	.04	.048	26	17	.26	61	.007	<1	.94	.002	.04	4	<1	1.2	2	<.01	3
B 171438	.5	20	22	40	.3	19	9	358	3.17	53	1	<2	4	13	.3	<.5	2.4	21	.15	.053	29	15	.28	54	.005	1	.91	.001	.04	2	<1	1.4	1	.01	3
B 171439	.7	29	35	50	.5	27	15	593	4.14	43	2	<2	3	14	.4	<.5	11.4	26	.18	.073	23	19	.27	57	.006	<1	1.14	.002	.05	2	<1	1.9	2	.01	2
B 171440	.8	28	29	43	.1	22	8	355	3.77	58	1	<2	5	4	.4	1.1	2.2	20	.03	.046	29	15	.17	36	.005	<1	.88	.001	.04	3	<1	1.2	1	.01	2
B 171441	.7	23	25	44	.1	18	6	188	3.83	50	1	<2	5	4	.3	.5	1.7	21	.03	.061	23	15	.16	47	.005	<1	.97	.001	.03	3	<1	1.1	2	.01	2
B 171442	.5	22	25	51	.1	20	7	256	4.41	83	1	<2	4	7	.4	<.5	2.7	17	.07	.126	24	14	.18	49	.003	<1	.81	<.001	.03	3	<1	1.0	1	.01	2
B 171443	.5	25	21	56	.2	23	10	447	3.64	52	1	<2	3	13	.4	<.5	1.3	26	.14	.082	30	16	.23	60	.008	<1	.90	.001	.05	2	<1	1.4	1	.01	3
B 171444	.6	40	30	70	.4	32	16	1925	4.42	60	4	<2	2	22	.5	.8	1.8	26	.19	.108	20	21	.26	90	.007	1	1.27	.003	.08	3	<1	2.2	3	.02	3
B 171445	.4	27	21	53	.3	25	12	824	3.33	45	3	<2	3	16	.3	.8	1.3	22	.16	.077	24	18	.28	71	.005	2	1.11	.002	.06	2	<1	1.7	<1	.01	3
B 171446	.9	37	24	51	.4	30	14	1202	3.72	60	3	<2	3	19	.4	1.2	1.6	21	.18	.100	23	17	.26	71	.004	1	1.10	.002	.07	2	<1	1.9	3	.02	2
B 171447	.3	20	17	54	.2	23	11	481	3.29	37	2	<2	6	11	.3	.7	<.5	21	.14	.073	32	20	.33	51	.007	<1	1.02	.001	.04	2	<1	1.7	2	<.01	2
B 171448	.4	22	15	50	.2	25	11	473	3.22	37	2	<2	4	12	.3	.6	<.5	23	.17	.071	31	21	.38	50	.009	<1	1.03	.002	.04	1	<1	1.7	<1	<.01	2
B 171449	.4	22	20	52	.2	26	13	565	3.50	54	2	<2	5	13	.3	.6	.7	24	.17	.070	29	21	.38	56	.008	<1	1.08	.002	.05	2	<1	1.9	1	<.01	2
B 171450	.5	31	19	54	.4	28	12	589	3.39	63	3	<2	3	18	.4	1.1	.7	24	.22	.091	25	22	.39	64	.009	1	1.13	.001	.05	2	<1	2.1	1	.02	2
RE B 171450	.6	31	20	56	.4	29	13	616	3.52	63	3	<2	3	19	.4	.8	.7	25	.23	.094	24	23	.40	65	.009	<1	1.17	.001	.05	2	<1	2.1	<1	.02	2
B 171451	.5	43	24	46	.3	26	10	323	3.33	80	4	<2	2	29	.6	1.0	1.1	27	.29	.090	24	21	.27	99	.008	1	1.08	.002	.07	2	<1	1.6	<1	.02	3
B 171452	.7	31	21	42	.3	22	5	241	2.80	69	3	<2	2	25	.4	1.4	.8	25	.26	.076	25	14	.19	75	.006	1	.88	.001	.05	2	<1	1.5	<1	.02	2
B 171453	.9	70	26	45	1.0	38	19	765	3.29	97	7	<2	2	39	.7	3.9	1.1	22	.37	.114	22	17	.20	71	.006	2	1.03	.003	.06	2	<1	2.3	1	.04	1
B 171454	.4	33	20	53	.1	29	13	652	3.29	49	1	<2	12	5	.4	.6	1.2	14	.03	.034	37	13	.23	69	.005	2	.75	<.001	.05	2	<1	2.4	1	<.01	1
B 171455	.6	30	19	50	.1	26	10	426	3.07	43	1	<2	9	6	.2	<.5	1.2	14	.06	.033	38	13	.22	53	.006	<1	.70	<.001	.04	2	<1	2.0	2	<.01	1
B 171456	.4	27	17	51	.3	22	9	383	2.96	32	1	<2	3	10	.3	.6	.8	24	.12	.054	28	22	.31	101	.007	1	1.19	.001	.07	2	<1	2.0	1	<.01	2
B 171457	.4	36	23	62	.4	26	13	711	3.49	38	2	<2	3	12	.5	<.5	.8	28	.16	.066	27	25	.32	121	.008	<1	1.32	.002	.09	2	<1	2.1	<1	.02	2
B 171458	.5	24	19	51	.5	23	11	513	3.00	32	2	<2	2	11	.4	<.5	.6	23	.16	.068	25	20	.30	88	.010	<1	1.05	.001	.07	2	<1	1.6	1	.02	2
B 171459	.6	47	37	78	.8	35	20	1087	4.53	42	2	<2	2	17	.7	<.5	1.7	36	.17	.121	25	30	.31	232	.008	<1	1.72	.004	.15	3	<1	2.5	2	.03	3
B 171460	.6	30	27	59	.4	27	14	683	3.38	36	2	<2	4	11	.3	.5	.8	25	.15	.056	29	20	.30	88	.013	<1	1.04	.001	.07	2	<1	2.0	2	.01	1
B 171461	.5	52	42	77	.7	38	18	1076	4.34	43	3	<2	4	20	.6	.6	.9	32	.26	.083	30	32	.40	156	.010	<1	1.56	.003	.12	2	<1	3.3	2	.02	2
B 171462	.5	29	25	58	.3	29	15	674	3.59	40	2	<2	5	12	.3	1.0	.9	26	.17	.061	32	22	.35	91	.009	<1	1.12	.001	.07	2	<1	2.1	1	.01	1
B 171463	.5	33	26	56	.6	27	13	597	3.47	35	2	<2	3	20	.4	<.5	.9	30	.28	.062	27	24	.34	138	.008	<1	1.24	.002	.08	3	<1	1.9	<1	.02	2
B 171464	.6	28	24	62	.3	30	15	576	3.88	40	2	<2	3	12	.3	.5	.6	29	.16	.056	27	25	.38	95	.011	1	1.19	.001	.07	3	<1	1.9	1	.01	1
B 171465	.6	42	26	70	.6	31	14	555	3.80	36	2	<2	3	18	.5	<.5	.8	40	.26	.074	26	28	.36	165	.011	<1	1.35	.002	.09	2	<1	1.9	1	.02	3
B 171466	.4	29	21	62	.3	26	11	486	3.37	32	2	<2	3	13	.3	.8	.7	35	.17	.051	28	27	.36	111	.013	1	1.23	.001	.07	2	<1	2.0	1	.01	2
B 171467	.4	23	21	54	.4	23	10	413	3.22	32	1	<2	4	11	.3	.6	.5	30	.15	.045	28	24	.40	94	.010	<1	1.18	.001	.06	2	<1	1.7	1	<.01	2
B 171468	.6	22	20	61	.1	26	11	360	3.55	36	1	<2	5	10	.3	.6	<.5	28	.13	.049	30	25	.39	95	.010	<1	1.21	.001	.06	2	<1	1.9	<1	<.01	1
STANDARD C3	26.4	70	35	165	5.7	35	11	785	3.22	57	24	2	20	29	24.6	14.2	22.8	82	.57	.092	19	168	.60	154	.085	22	1.83	.040	.16	15	1	4.4	1	.03	6
STANDARD G-2	1.5	3	2	43	<.1	7	3	560	2.05	<1	4	<2	5	78	<.2	<.5	<.5	41	.66	.104	9	77	.61	232	.129	<1	.98	.080	.49	2	<1	2.7	<1	<.01	4

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data A FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 171469	.6	29	23	65	.4	29	12	330	4.00	37	1	<2	5	10	.5	.6	<.5	35	.14	.058	34	29	.39	175	.009	3	1.46	.004	.09	2	<1	2.4	<1	.01	4
B 171470	.8	34	30	68	.3	32	12	408	4.50	46	1	<2	4	13	.4	<.5	1.2	35	.19	.061	26	31	.36	169	.010	3	1.52	.003	.10	2	<1	2.3	<1	.02	4
B 171471	.8	35	31	61	.4	32	16	785	4.00	59	2	<2	5	18	.4	.6	1.9	27	.26	.076	31	21	.32	190	.005	3	1.30	.003	.09	3	<1	2.8	1	.02	3
B 171472	.6	26	21	46	.3	25	10	408	3.26	49	1	<2	5	11	.3	.5	1.4	23	.13	.053	34	19	.30	156	.004	3	1.10	.002	.06	3	<1	2.3	<1	.01	3
B 171473	.8	38	32	57	.4	37	18	1004	3.76	56	2	<2	5	13	.3	.5	1.8	24	.18	.069	32	21	.35	151	.005	4	1.23	.003	.08	3	<1	3.3	<1	.01	3
B 171474	.8	38	31	59	.5	37	16	640	3.67	54	1	<2	6	10	.3	.6	1.5	21	.14	.065	34	18	.33	106	.005	<1	1.00	.002	.06	3	<1	2.9	<1	.01	2
B 171475	.9	47	29	61	.3	38	16	735	4.14	72	2	<2	6	12	.3	.8	2.0	23	.17	.072	33	24	.38	147	.005	2	1.23	.002	.08	4	<1	3.6	1	.02	3
B 171476	.9	40	30	53	.1	33	16	698	3.74	56	1	<2	8	9	.3	.8	1.6	22	.11	.041	41	18	.36	84	.004	1	1.03	.001	.06	3	<1	2.7	1	<.01	2
B 171477	1.2	37	31	64	.3	35	18	560	4.65	55	2	<2	4	14	.3	.5	2.0	29	.19	.072	28	26	.35	103	.008	3	1.29	.002	.07	4	<1	2.6	<1	.02	3
B 171478	.9	27	25	60	.1	26	11	326	4.28	49	<1	<2	5	9	.4	.9	1.3	26	.09	.049	30	23	.32	84	.006	2	1.19	<.001	.05	2	<1	1.7	<1	.01	3
B 171479	1.0	29	27	60	.1	30	12	425	4.32	55	<1	<2	6	8	.3	.9	1.2	26	.07	.047	35	22	.34	73	.007	3	1.05	<.001	.05	2	<1	1.7	1	<.01	3
B 171480	.9	37	24	53	.4	36	14	734	3.80	49	2	<2	4	15	.3	.5	1.4	25	.18	.070	29	22	.32	61	.007	2	1.27	.002	.07	2	<1	2.4	<1	.01	2
B 171481	1.2	41	27	49	.5	34	18	1142	4.11	60	3	<2	3	17	.3	1.0	1.6	22	.20	.127	24	20	.23	59	.006	2	1.23	.002	.08	2	<1	2.3	<1	.03	2
B 171482	1.4	22	24	31	.2	15	5	144	3.56	43	<1	<2	5	4	.3	.7	1.8	21	.04	.081	28	15	.15	40	.005	1	.83	<.001	.03	2	<1	.9	1	.02	2
B 171483	.9	15	26	37	.4	14	5	164	3.94	35	<1	<2	3	5	.2	<.5	1.1	27	.07	.110	23	19	.17	53	.007	<1	.90	<.001	.04	3	<1	.9	<1	.02	2
B 171484	1.4	25	37	41	.1	23	8	247	3.54	60	<1	<2	5	6	.2	<.5	2.8	15	.04	.066	35	12	.13	57	.004	1	.61	<.001	.04	2	<1	.9	1	<.01	1
B 171485	1.0	20	30	43	.1	20	7	223	3.96	59	1	<2	5	10	.2	.7	1.7	19	.12	.096	26	17	.21	68	.005	2	.82	<.001	.04	3	<1	1.2	<1	.01	1
RE B 171485	1.0	21	31	47	.1	22	8	233	4.18	61	1	<2	5	11	.3	.7	1.8	20	.13	.102	27	18	.22	73	.005	2	.86	<.001	.04	3	<1	1.2	1	.02	1
B 171486	1.0	24	26	48	.2	22	8	258	4.49	53	1	<2	6	11	.4	.8	.8	30	.13	.080	30	24	.29	66	.007	2	1.15	.001	.05	2	<1	1.7	<1	.01	3
B 171487	.9	39	33	66	.3	32	18	698	4.32	63	2	<2	3	19	.3	.8	.9	26	.23	.104	24	20	.24	67	.009	2	.94	.001	.06	2	<1	1.7	1	.02	2
B 171488	.8	46	44	62	.4	32	20	1177	4.08	61	4	<2	2	28	.5	1.0	1.7	27	.33	.113	22	21	.24	76	.008	1	1.11	.002	.07	2	<1	1.9	<1	.03	2
B 171489	.9	66	37	60	1.0	45	18	1980	4.22	84	9	<2	5	34	.9	1.0	1.2	26	.35	.164	25	22	.25	96	.009	4	1.50	.003	.09	2	<1	5.5	<1	.03	2
B 171490	2.3	85	32	96	.5	58	18	446	6.85	144	3	<2	6	20	.5	2.0	4.2	29	.14	.112	27	33	.20	73	.007	3	1.24	.002	.08	3	<1	2.5	1	.02	4
B 171491	.6	26	22	54	.1	29	14	507	3.24	55	2	<2	7	15	.2	<.5	<.5	19	.18	.058	38	20	.36	43	.008	3	.94	.001	.05	2	<1	2.1	<1	<.01	2
B 171492	.8	31	15	40	.2	22	9	399	2.68	77	2	<2	4	18	.2	1.5	1.1	13	.18	.077	31	10	.16	35	.004	2	.54	<.001	.04	1	<1	1.5	<1	.02	<1
B 171493	.6	62	22	51	1.3	39	14	850	3.56	72	7	<2	2	45	.6	.8	.9	19	.45	.158	21	15	.20	60	.007	3	.92	.002	.07	2	<1	2.9	<1	.05	1
B 171494	.7	46	35	77	.5	45	20	979	4.32	48	1	<2	8	12	.4	.8	1.2	23	.15	.056	37	23	.38	137	.009	1	1.17	.003	.08	2	<1	3.7	<1	.01	2
B 171495	1.0	76	49	90	1.8	59	24	1109	5.85	71	3	<2	9	32	.5	.8	2.6	37	.41	.145	40	38	.39	286	.008	5	2.12	.005	.17	3	<1	8.2	1	.02	5
B 171496	1.0	64	42	83	1.7	50	20	963	5.15	62	3	<2	5	29	.4	.6	2.2	33	.38	.158	32	32	.36	244	.007	4	1.83	.004	.14	3	<1	6.0	<1	.04	4
B 171497	.6	58	40	78	1.1	47	20	1090	4.58	55	3	<2	5	30	.5	<.5	1.9	30	.43	.117	30	31	.35	242	.008	3	1.61	.003	.12	3	<1	4.7	<1	.03	3
B 171498	.8	39	34	70	.4	37	17	887	3.95	50	2	<2	5	19	.4	.7	1.1	27	.29	.085	27	27	.33	180	.007	3	1.32	.002	.10	2	<1	3.6	<1	.02	2
B 171499	.7	38	28	65	.5	35	15	660	3.88	57	2	<2	5	15	.4	.6	2.0	24	.21	.078	30	22	.31	139	.006	2	1.17	.002	.08	2	<1	3.1	<1	.02	1
B 171500	1.3	61	79	60	.6	43	20	2192	4.64	67	5	<2	3	29	.4	.6	3.0	28	.36	.133	25	22	.31	183	.006	4	1.44	.004	.11	3	<1	3.1	1	.04	2
B 171501	.6	39	35	47	.3	30	11	289	3.20	47	2	<2	7	8	.2	.9	1.6	20	.07	.044	35	19	.31	61	.005	2	1.02	.001	.06	3	<1	2.7	<1	<.01	1
B 171502	1.2	60	55	60	.5	44	20	1140	4.55	73	4	<2	5	19	.3	1.1	2.7	22	.21	.092	26	21	.30	90	.006	3	1.19	.002	.08	5	<1	3.4	<1	.02	1
STANDARD C3	26.7	69	34	167	5.5	36	11	809	3.31	56	24	2	20	29	24.7	15.6	22.3	83	.59	.092	21	180	.61	160	.089	24	1.81	.038	.16	15	1	4.5	<1	.03	6
STANDARD G-2	1.7	3	3	46	<.1	7	4	574	2.03	<1	3	<2	4	75	<.2	<.5	<.5	42	.69	.105	9	85	.62	242	.137	3	.98	.085	.49	3	<1	2.6	<1	<.01	5

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 171503	1.0	75	41	76	.5	49	20	1092	5.06	75	4	<2	8	19	.6	.7	3.0	26	.20	.088	31	23	.34	88	.005	5	1.45	.004	.10	4	<1	4.3	1	.01	2
B 171504	1.4	104	45	95	1.1	74	31	1851	6.42	81	7	<2	6	32	.6	.7	3.4	30	.33	.147	21	31	.34	140	.006	6	2.05	.006	.17	2	<1	5.8	<1	.04	4
B 171505	1.1	78	37	85	.7	57	28	1175	5.49	68	5	<2	7	27	.5	.8	2.3	30	.29	.097	23	28	.35	107	.007	5	1.73	.005	.13	2	<1	4.6	1	.02	3
B 171506	.9	97	34	56	.7	53	22	947	4.01	45	7	<2	5	23	.7	.7	1.9	25	.29	.074	24	24	.29	79	.006	4	1.34	.003	.08	2	<1	3.4	<1	.02	1
B 171507	1.0	59	28	71	.6	46	28	1575	4.57	58	5	<2	3	21	.5	.9	1.4	18	.27	.112	18	18	.22	72	.005	5	1.09	.003	.08	2	<1	3.0	1	.03	1
B 171508	.6	22	24	60	.2	19	7	224	3.79	28	1	<2	3	8	.6	.5	.6	31	.08	.062	23	23	.26	101	.009	1	1.12	.001	.04	1	<1	1.2	<1	.01	2
B 171509	.8	22	25	75	.1	21	8	277	4.52	30	1	<2	3	16	.6	<.5	<.5	33	.22	.065	22	24	.29	75	.011	3	1.16	.001	.05	2	<1	1.4	<1	.01	2
B 171510	.6	25	20	66	.1	27	11	316	3.98	33	2	<2	4	16	.5	.7	<.5	31	.24	.102	25	24	.40	69	.011	2	1.19	.002	.05	2	<1	1.6	<1	.01	2
B 171511	.8	31	26	78	.2	28	13	464	4.18	45	2	<2	4	17	.5	.8	1.0	29	.23	.083	27	22	.26	62	.011	2	1.04	.001	.06	2	<1	1.7	<1	.01	2
B 171512	1.2	35	23	64	.2	32	14	503	3.48	48	2	<2	4	18	.5	.9	.7	20	.20	.081	26	16	.24	60	.009	1	.86	.001	.06	2	<1	2.2	<1	.01	1
RE B 171512	1.1	35	22	64	.2	32	14	509	3.49	47	3	<2	4	17	.5	.8	.7	20	.20	.081	26	16	.24	59	.010	2	.86	.002	.06	2	<1	2.2	1	.01	1
B 171513	1.0	38	24	60	.1	36	14	765	3.45	40	3	<2	3	20	.5	1.1	.5	24	.24	.088	22	20	.27	96	.008	<1	1.08	.002	.09	2	<1	2.3	<1	.02	1
B 171514	1.3	61	30	62	.3	38	15	509	3.80	53	5	<2	5	28	.7	.7	.9	26	.29	.112	26	19	.24	90	.010	<1	1.05	.002	.08	2	<1	3.6	1	.02	1
B 171515	2.0	62	30	66	.7	45	15	785	3.70	104	6	<2	2	38	.7	4.7	2.7	19	.37	.139	17	15	.20	62	.007	1	.90	.002	.06	2	<1	2.5	<1	.04	<1
B 171516	2.2	114	43	71	.9	66	23	1549	4.77	118	10	<2	3	57	1.1	1.5	4.3	27	.54	.221	17	24	.29	114	.010	3	1.51	.004	.11	2	<1	4.4	<1	.06	2
B 171517	.7	162	56	59	1.5	76	17	1520	4.23	108	14	<2	2	73	1.5	2.2	2.3	24	.84	.214	19	20	.23	87	.010	<1	1.36	.003	.07	1	<1	3.4	<1	.07	2
B 171518	.6	94	52	64	.6	54	24	1232	4.32	72	10	<2	3	53	1.1	.7	2.0	26	.68	.145	20	22	.23	85	.011	2	1.37	.003	.08	2	<1	4.3	<1	.05	2
STANDARD C3	26.0	69	35	175	5.3	35	11	772	3.16	55	24	2	20	28	25.3	15.8	21.8	80	.56	.089	19	169	.58	150	.085	19	1.79	.035	.15	15	1	4.3	<1	.02	6
STANDARD G-2	1.7	3	3	48	<.1	7	4	551	1.97	<1	4	<2	5	73	<.2	<.5	<.5	41	.66	.099	9	80	.60	229	.131	<1	.98	.078	.48	3	<1	2.6	<1	<.01	4

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

ACME (YTICAL LABORATORIES LTD. 852 E. HASTINGS ST. (COUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604(3-1716
(9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003152 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** ppb
B 171151	186
B 171152	295
B 171153	65
B 171154	34
B 171155	66
B 171156	20
B 171157	104
B 171158	105
B 171159	26
B 171160	254
B 171161	59
B 171162	45
B 171163	45
B 171164	26
B 171165	70
B 171166	46
B 171167	37
B 171168	149
B 171169	376
B 171170	215
RE B 171162	50
B 171171	193
B 171172	187
B 171173	2620
B 171174	62
B 171175	34
B 171176	333
B 171177	67
B 171178	130
B 171179	37
B 171180	50
B 171181	52
B 171182	92
B 171183	79
B 171184	63
STANDARD AU-S	51

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SOIL SS80 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: AUG 22 2000 DATE REPORT MAILED: Aug 30/00 SIGNED BY: C. Leong D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data FA

SAMPLE#	Au** ppb
B 171185	144
B 171186	41
B 171187	68
B 171188	93
B 171189	95
B 171190	37
B 171191	533
B 171192	62
B 171193	106
B 171194	48
B 171195	133
B 171196	47
B 171197	44
B 171198	99
B 171199	38
B 171200	111
RE B 171199	44
B 171201	177
B 171202	69
B 171203	81
B 171204	170
B 171205	125
B 171206	345
B 171207	56
B 171208	37
B 171209	55
B 171210	21
B 171211	25
B 171212	63
B 171213	49
B 171214	95
B 171215	62
B 171216	49
B 171217	43
B 171218	115
STANDARD AU-S	48

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ___

SAMPLE#	Au** ppb
B 171219	58
B 171220	32
B 171221	60
B 171222	35
B 171223	38
B 171224	70
B 171225	10
B 171226	66
B 171227	21
B 171228	68
B 171229	60
B 171230	160
B 171231	29
B 171232	24
B 171233	73
B 171234	22
B 171235	76
B 171236	27
B 171237	46
B 171238	32
B 171239	18
B 171240	27
RE B 171243	209
B 171241	119
B 171242	28
B 171243	168
B 171244	30
B 171245	64
B 171246	28
B 171247	29
B 171248	137
B 171249	136
B 171250	134
B 171251	35
B 171252	60
STANDARD AU-S	49

Sample type: SOIL S$80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA___

SAMPLE#	Au** ppb
B 171253	17
B 171254	20
B 171255	43
B 171256	41
B 171257	57
B 171258	69
B 171259	203
B 171260	56
B 171261	76
B 171262	151
B 171263	115
B 171264	25
B 171265	22
B 171266	563
B 171267	38
B 171268	60
B 171269	81
B 171270	57
RE B 171270	112
B 171271	69
B 171272	88
B 171273	133
B 171274	28
B 171275	42
B 171276	14
B 171277	41
B 171278	51
B 171279	66
B 171280	167
B 171281	18
B 171282	66
B 171283	68
B 171284	36
B 171285	41
B 171286	98
STANDARD AU-S	47

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA

SAMPLE#	Au** ppb
B 171287	165
B 171288	74
B 171289	93
B 171290	40
B 171291	158
B 171292	90
B 171293	40
B 171294	56
B 171295	44
B 171296	41
B 171297	40
B 171298	79
B 171299	43
B 171300	21
RE B 171300	20
B 171301	134
B 171302	148
B 171303	75
B 171304	85
B 171305	35
B 171306	31
B 171307	85
B 171308	303
B 171519	147
B 171520	96
B 171521	25
B 171522	29
B 171523	59
B 171524	80
B 171525	99
B 171526	134
B 171527	132
B 171528	304
B 171529	498
B 171530	128
STANDARD AU-S	49

Sample type: SOIL S80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** ppb
B 171531	265
B 171532	520
B 171533	62
B 171534	22
B 171535	156
B 171536	69
B 171537	84
B 171538	45
B 171539	46
B 171540	115
B 171541	156
B 171542	35
B 171543	44
B 171544	72
B 171545	33
RE B 171545	17
B 171546	117
B 171547	11
B 171548	242
B 171549	67
B 171550	438
STANDARD AU-S	47

Sample type: SOIL S880 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Date FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. COUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003152R Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 171151	.9	25	20	55	.2	20	8	269	3.79	76	1	<2	4	7	.5	.5	2.0	31	.04	.076	26	15	.10	43	.012	<1	.70	.003	.05	3	<1	1.2	1	<.01	3
B 171152	.7	25	16	37	.2	17	5	127	3.35	70	1	<2	4	7	.4	.6	1.2	31	.03	.063	27	14	.06	54	.013	<1	.58	.002	.03	2	<1	1.1	2	<.01	2
B 171153	1.0	28	19	61	.2	26	16	545	3.43	37	1	<2	2	17	.3	<.5	<.5	24	.21	.073	22	16	.18	78	.006	<1	.86	.004	.06	2	<1	1.3	1	.01	3
B 171154	1.0	36	21	76	.2	37	16	725	3.79	34	2	<2	6	16	.5	<.5	<.5	26	.20	.075	26	24	.39	74	.006	<1	1.31	.004	.08	2	<1	3.1	<1	.01	3
B 171155	1.5	33	25	65	.2	35	15	547	3.70	44	2	<2	6	14	.4	.8	1.2	23	.18	.065	26	23	.40	55	.006	<1	1.17	.004	.06	3	<1	2.7	<1	<.01	3
B 171156	1.5	26	13	61	.2	31	13	412	3.44	24	1	<2	6	11	.3	.6	<.5	25	.14	.051	27	24	.49	47	.007	<1	1.24	.004	.05	1	<1	2.4	<1	<.01	3
B 171157	2.9	42	22	70	.5	41	18	783	4.32	50	3	<2	4	13	.5	.9	<.5	23	.15	.063	24	21	.26	68	.007	<1	1.06	.003	.07	2	<1	2.6	1	.02	3
B 171158	.6	28	15	60	<.1	29	9	292	2.72	17	1	<2	9	7	<.2	.7	<.5	19	.07	.040	38	20	.31	57	.016	<1	.92	.003	.05	1	<1	2.1	<1	<.01	2
B 171159	.3	10	13	24	.5	8	3	117	1.88	15	<1	<2	1	5	<.2	<.5	<.5	22	.04	.039	25	14	.16	79	.009	<1	.87	.003	.05	1	<1	.9	1	<.01	3
B 171160	.5	28	35	60	.4	25	10	302	3.44	35	1	<2	4	8	.3	.8	<.5	29	.11	.062	27	24	.29	99	.012	<1	1.22	.004	.08	2	<1	2.1	<1	.01	3
B 171161	.7	27	64	52	.4	18	6	177	3.85	27	1	<2	3	9	.5	<.5	<.5	31	.11	.055	22	24	.26	106	.009	<1	1.23	.004	.08	2	<1	1.5	<1	.02	4
B 171162	.2	12	12	31	.2	11	4	114	1.75	13	<1	<2	1	7	<.2	<.5	<.5	23	.06	.036	26	13	.14	88	.010	<1	.71	.002	.06	1	<1	.9	<1	<.01	3
B 171163	.6	22	18	61	.2	26	10	335	3.11	27	1	<2	4	11	.4	<.5	<.5	31	.13	.040	26	24	.35	95	.014	<1	1.04	.004	.08	1	<1	1.9	<1	<.01	3
B 171164	.7	47	36	71	1.2	39	19	1354	4.42	47	2	<2	2	29	.6	1.1	<.5	40	.41	.113	20	32	.40	174	.008	<1	1.67	.006	.13	2	<1	3.3	<1	.04	5
B 171165	.8	62	38	66	.7	49	19	1290	4.35	110	3	<2	5	27	.6	1.0	.6	33	.28	.109	24	30	.41	132	.006	<1	1.74	.006	.11	2	<1	5.1	<1	.03	4
B 171166	.5	25	19	54	.1	21	8	211	4.35	39	1	<2	8	5	.5	.7	<.5	34	.06	.046	29	25	.29	75	.011	<1	1.16	.002	.05	2	<1	1.9	1	.01	4
B 171167	.3	11	6	35	.2	11	7	266	2.21	18	1	<2	1	6	.2	.7	<.5	19	.08	.056	20	10	.05	67	.006	<1	.57	.003	.04	1	<1	.9	<1	.01	3
B 171168	.6	32	19	91	.6	37	19	854	4.93	56	2	<2	4	19	.6	.8	1.5	34	.21	.088	20	29	.35	121	.009	<1	1.71	.005	.08	2	<1	2.7	<1	.02	6
B 171169	.9	42	20	87	.7	40	22	1289	5.05	89	3	<2	2	21	.6	.5	1.5	29	.21	.103	19	28	.30	108	.008	<1	1.43	.004	.08	3	<1	2.4	<1	.02	6
B 171170	1.3	20	16	43	.1	21	8	302	3.06	86	1	<2	3	7	.4	.5	.8	24	.06	.060	25	10	.04	32	.008	<1	.50	.002	.03	2	<1	1.1	2	.01	3
RE B 171170	1.3	20	17	44	.1	22	8	311	3.09	88	1	<2	3	7	.4	.6	.8	26	.06	.061	25	11	.04	32	.008	<1	.50	.003	.03	3	<1	1.1	1	.01	3
B 171171	2.0	53	34	102	.7	49	28	1479	5.30	120	4	<2	3	20	.9	.8	2.1	26	.19	.120	21	24	.21	90	.008	<1	1.33	.004	.08	3	<1	3.4	1	.03	6
B 171172	1.7	46	27	65	.6	44	21	1384	4.55	73	3	<2	6	20	.6	.6	4.1	25	.20	.090	27	23	.27	98	.005	<1	1.53	.004	.09	2	<1	4.1	1	.01	5
B 171173	1.6	26	18	53	.4	26	10	315	4.66	107	1	2	2	9	.5	.6	<.5	28	.09	.065	25	14	.10	57	.011	<1	.58	.002	.04	3	<1	1.0	2	.01	4
B 171174	1.2	25	24	70	.2	25	10	322	5.13	48	1	<2	3	12	.5	.6	<.5	25	.13	.093	21	21	.22	97	.008	<1	1.03	.003	.05	3	<1	1.3	<1	.02	5
B 171175	.9	32	24	76	.4	25	12	389	4.15	35	2	<2	3	21	.6	.5	<.5	31	.19	.107	20	22	.19	111	.007	<1	1.23	.004	.07	1	<1	1.9	1	.02	4
B 171176	1.5	32	18	65	.2	32	13	341	3.85	51	2	<2	3	12	.6	.7	<.5	22	.14	.066	23	17	.24	61	.006	<1	1.04	.003	.06	2	<1	1.7	<1	.01	3
B 171177	.8	22	19	52	.5	22	16	613	3.06	27	1	<2	2	9	.4	.7	<.5	25	.10	.061	22	23	.27	122	.007	<1	1.14	.004	.10	2	<1	1.6	<1	.02	4
B 171178	.7	29	21	64	.2	25	12	693	3.53	35	1	<2	2	8	.5	.8	<.5	28	.06	.083	21	24	.27	140	.008	<1	1.26	.004	.11	2	<1	2.1	<1	.02	4
B 171179	.6	31	24	61	.7	25	13	759	3.21	36	1	<2	2	17	.5	.9	.5	26	.23	.085	22	22	.31	140	.007	<1	1.18	.003	.09	2	<1	2.1	<1	.02	4
B 171180	.5	31	19	60	.5	28	14	638	3.45	36	1	<2	5	10	.5	.5	<.5	28	.11	.054	26	24	.37	89	.011	<1	1.18	.004	.08	2	<1	2.6	1	<.01	4
B 171181	.4	24	17	49	.2	18	7	216	2.63	25	1	<2	2	9	.4	<.5	<.5	32	.11	.050	25	19	.22	128	.010	<1	1.00	.003	.06	1	<1	1.5	<1	.02	4
B 171182	.8	55	29	70	.8	38	16	745	4.43	75	3	<2	4	27	.6	1.0	1.1	29	.35	.123	24	25	.33	166	.006	<1	1.52	.004	.10	2	<1	4.1	<1	.02	6
B 171183	1.0	86	40	77	.8	56	28	2695	5.01	76	5	<2	5	26	.6	.9	1.3	27	.35	.136	23	28	.35	146	.007	<1	1.67	.006	.11	2	<1	5.6	1	.03	6
B 171184	.6	30	20	42	.2	21	8	352	2.79	31	2	<2	1	20	.3	.5	<.5	23	.27	.055	24	15	.22	90	.009	<1	.80	.003	.05	1	<1	1.3	<1	.01	4
STANDARD C3	27.8	71	36	174	5.8	36	12	795	3.34	57	25	<2	22	29	24.9	17.4	22.7	82	.58	.096	20	175	.61	158	.084	20	1.88	.041	.16	15	1	4.6	<1	.03	6
STANDARD G-2	1.7	3	4	48	<.1	8	4	549	2.05	<1	3	<2	4	75	<.2	<.5	<.5	43	.66	.106	9	81	.62	245	.128	<1	.99	.099	.51	3	<1	2.6	1	<.01	5

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
- SAMPLE TYPE: SOIL PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: NOV 23 2000 DATE REPORT MAILED: Nov 28/00 SIGNED BY: ..D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 171185	1.0	38	18	60	.5	35	17	1344	3.83	51	2	<2	5	14	.6	.8	1.1	19	.18	.069	24	18	.30	71	.005	1	1.00	.004	.05	2	<1	3.0	<1	.02	3
B 171186	.6	24	15	66	.1	22	13	703	4.19	33	1	<2	3	6	.5	1.0	<.5	34	.06	.072	25	20	.16	90	.015	1	.89	.004	.05	2	<1	1.5	<1	.01	4
B 171187	.5	36	14	76	.3	30	12	445	4.21	38	1	<2	6	7	.6	1.6	<.5	27	.04	.060	25	21	.18	69	.009	1	1.19	.004	.05	2	<1	2.6	<1	.01	4
B 171188	1.0	48	29	69	.5	43	20	870	4.64	59	3	<2	3	19	.5	.5	1.0	28	.23	.087	24	24	.24	68	.009	1	1.21	.004	.07	2	<1	2.9	<1	.02	4
B 171189	.6	20	13	47	.2	22	10	342	2.48	26	1	<2	6	7	.2	<.5	<.5	18	.09	.039	33	17	.28	58	.012	1	.72	.003	.05	1	<1	1.8	1	<.01	2
B 171190	.7	46	28	63	.8	32	13	689	3.80	34	2	<2	2	17	.6	.9	<.5	30	.21	.089	23	27	.31	166	.009	1	1.29	.005	.10	2	<1	2.4	<1	.03	4
B 171191	.9	39	30	54	.6	30	13	767	3.21	61	1	<2	3	13	.6	.9	.9	19	.18	.064	22	15	.23	81	.007	<1	.73	.002	.05	2	<1	2.1	<1	.02	2
B 171192	.7	25	25	52	.7	23	11	348	3.44	32	1	<2	5	14	.4	<.5	.8	28	.15	.061	25	22	.28	189	.009	2	1.04	.004	.09	2	<1	2.5	<1	.01	3
B 171193	1.0	37	31	67	1.3	34	20	1332	4.06	42	2	<2	3	15	.6	.7	.7	27	.19	.090	24	26	.31	183	.008	1	1.24	.005	.10	2	<1	2.7	<1	.03	4
B 171194	.6	31	28	57	1.4	27	10	486	3.30	29	2	<2	3	14	.6	.7	.6	27	.17	.088	26	28	.33	182	.008	<1	1.25	.005	.10	2	<1	2.8	<1	.02	4
B 171195	.7	35	24	62	.3	33	13	691	3.56	38	1	<2	5	12	.5	<.5	.6	24	.17	.056	31	24	.33	109	.012	<1	.94	.003	.06	2	<1	2.8	<1	.01	3
B 171196	.6	32	24	57	.6	29	12	537	3.43	35	2	<2	3	14	.5	.8	.7	27	.18	.071	24	24	.30	156	.007	<1	1.15	.005	.09	2	<1	2.4	<1	.02	3
B 171197	.6	40	26	66	.5	33	14	581	3.97	37	2	<2	8	12	.6	<.5	<.5	32	.14	.052	29	29	.35	191	.009	<1	1.38	.004	.09	2	<1	3.8	<1	.01	3
B 171198	.9	30	24	62	.4	31	15	814	3.58	42	2	<2	4	19	.4	.9	.7	24	.28	.056	25	23	.37	142	.007	<1	1.05	.005	.07	2	<1	2.3	<1	.02	3
B 171199	.3	28	21	60	.2	30	14	439	3.65	34	2	<2	5	15	.4	<.5	<.5	28	.23	.048	26	27	.43	104	.007	<1	1.22	.004	.06	2	<1	2.2	<1	.01	3
B 171200	.7	34	28	51	.3	30	13	612	3.44	43	2	<2	4	8	.5	.6	1.1	18	.07	.065	23	18	.27	89	.005	1	1.01	.003	.05	2	<1	2.5	<1	.02	2
RE B 171200	.7	33	29	51	.3	30	13	612	3.47	43	2	<2	4	8	.5	.6	1.0	18	.07	.064	24	18	.27	90	.005	<1	1.01	.002	.05	2	<1	2.5	<1	.02	2
B 171201	.8	33	26	54	.4	32	12	531	3.60	46	2	<2	4	18	.4	<.5	1.0	20	.21	.062	24	21	.32	153	.004	<1	1.02	.005	.07	2	<1	2.2	<1	.02	2
B 171202	.5	27	21	63	.1	29	11	363	4.27	35	1	<2	7	8	.5	.6	<.5	29	.09	.048	32	31	.43	84	.012	<1	1.20	.003	.05	2	<1	2.0	<1	.01	3
B 171203	.5	37	28	60	.3	36	16	776	3.75	39	3	<2	6	17	.5	<.5	.6	27	.23	.074	28	25	.40	57	.010	<1	1.16	.003	.06	2	<1	3.2	<1	.01	3
B 171204	1.1	54	38	63	.4	44	18	1030	4.10	50	5	<2	5	24	.6	<.5	1.6	21	.34	.091	23	21	.35	66	.006	<1	1.17	.004	.06	2	<1	3.5	<1	.02	3
B 171205	1.3	56	31	75	.6	49	21	1620	4.63	60	6	<2	3	27	.6	.6	1.1	22	.34	.102	18	20	.27	77	.007	<1	1.15	.004	.07	2	<1	2.9	<1	.03	3
B 171206	1.7	63	26	65	1.3	54	22	2003	4.71	61	8	<2	2	42	.8	<.5	<.5	19	.61	.180	14	18	.23	78	.007	1	1.18	.006	.07	2	<1	3.2	<1	.06	3
B 171207	.9	31	18	54	.2	31	13	569	3.58	41	2	<2	3	18	.4	.8	<.5	21	.24	.090	20	17	.25	57	.009	<1	.81	.003	.05	2	<1	1.6	<1	.02	2
B 171208	1.4	32	17	62	.2	34	11	301	4.12	72	2	<2	2	15	.6	2.7	<.5	25	.14	.077	19	15	.14	49	.007	<1	.62	.002	.04	2	<1	1.2	<1	.01	2
B 171209	.6	32	27	62	.4	30	18	797	4.39	67	3	<2	2	24	.7	<.5	<.5	33	.35	.105	20	22	.27	82	.010	<1	1.13	.004	.05	2	<1	2.1	<1	.02	3
B 171210	1.7	36	16	65	.1	40	11	356	3.80	35	1	<2	3	5	.6	<.5	<.5	23	.05	.072	29	11	.06	48	.007	<1	.61	.002	.03	1	<1	1.1	1	.01	2
B 171211	.7	31	30	57	.4	27	11	449	4.10	39	2	<2	3	19	.5	.6	1.9	32	.27	.058	25	23	.26	71	.009	<1	1.18	.003	.06	2	<1	2.1	<1	.01	3
B 171212	.6	42	29	77	1.0	35	16	787	4.47	39	2	<2	3	14	.6	.5	.5	34	.14	.099	25	33	.37	200	.008	<1	1.68	.005	.13	2	<1	3.3	<1	.03	4
B 171213	.4	32	25	68	.4	31	16	1044	4.09	37	2	<2	4	13	.5	.5	<.5	30	.18	.066	23	29	.37	170	.008	<1	1.30	.004	.10	2	<1	2.3	<1	.02	3
B 171214	.5	19	18	55	.3	23	10	372	3.10	35	1	<2	3	9	.4	<.5	1.4	24	.11	.042	24	23	.33	103	.007	<1	1.01	.003	.07	1	<1	1.6	<1	.01	2
B 171215	.5	31	30	81	.3	35	16	957	4.52	39	1	<2	4	12	.5	<.5	<.5	37	.12	.074	21	34	.36	192	.008	1	1.56	.005	.13	2	<1	2.5	1	.02	4
B 171216	.4	24	19	62	<.1	29	12	356	3.20	31	1	<2	6	6	.4	.7	<.5	24	.09	.035	27	23	.35	90	.009	<1	.98	.002	.06	1	<1	1.8	<1	<.01	2
B 171217	.4	32	33	70	<.1	34	13	638	4.71	46	1	<2	5	11	.5	<.5	<.5	23	.17	.050	22	28	.34	105	.007	<1	1.23	.003	.07	2	<1	1.8	<1	.01	2
B 171218	.7	38	32	65	.3	36	16	605	4.17	52	3	<2	9	17	.5	.8	.8	24	.21	.065	29	23	.36	126	.006	<1	1.26	.004	.08	2	<1	3.8	<1	.01	2
STANDARD C3	28.9	70	36	170	6.3	36	11	836	3.48	58	27	<2	23	29	24.9	17.8	24.0	86	.61	.089	21	181	.64	167	.088	23	1.89	.041	.16	16	1	4.9	<1	.03	6
STANDARD G-2	1.5	3	3	44	<.1	7	4	545	2.02	<1	4	<2	5	72	<.2	<.5	<.5	42	.66	.097	9	80	.62	242	.129	<1	.93	.092	.49	2	<1	2.6	<1	<.01	4

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 171219	.7	36	28	67	.5	38	17	921	4.10	42	3	<2	4	21	.4	.7	1.8	27	.31	.082	27	27	.40	117	.007	2	1.40	.004	.10	2	<1	2.9	<1	.02	2
B 171220	.7	30	24	67	.2	32	14	477	3.73	36	1	<2	5	14	.3	.5	1.2	28	.16	.055	31	25	.35	90	.007	2	1.21	.003	.08	2	<1	2.2	<1	.01	2
B 171221	.6	25	19	52	.2	26	13	348	3.54	30	1	<2	6	9	.3	<.5	1.0	30	.11	.043	33	27	.37	77	.008	<1	1.18	.002	.06	2	<1	2.1	<1	.01	2
B 171222	.6	25	20	50	.2	31	12	363	3.54	34	1	<2	6	13	.3	<.5	.8	27	.19	.039	34	26	.43	57	.008	<1	1.15	.001	.05	2	<1	2.1	<1	<.01	1
B 171223	1.0	66	32	68	.4	54	24	1626	4.47	48	5	<2	6	23	.5	<.5	1.7	26	.31	.082	26	28	.45	93	.006	1	1.54	.004	.10	2	<1	4.1	1	.02	2
B 171224	.9	24	19	61	.1	28	10	388	4.22	33	<1	<2	5	8	.3	.6	1.2	26	.09	.062	32	25	.35	65	.007	<1	1.10	<.001	.05	2	<1	1.5	<1	<.01	2
B 171225	.8	25	24	67	.1	35	13	380	4.25	34	1	<2	6	6	.4	<.5	.8	29	.10	.056	31	32	.47	71	.012	1	1.32	.001	.05	2	<1	1.9	1	.01	2
B 171226	.7	17	19	60	.1	21	7	225	4.16	33	<1	<2	4	6	.4	<.5	1.0	33	.06	.053	26	26	.29	69	.010	1	1.15	.001	.04	2	<1	1.4	<1	.01	2
B 171227	.9	34	14	59	.3	42	15	359	3.33	34	2	<2	2	18	.3	.5	<.5	20	.25	.072	27	10	.11	60	.006	2	.53	<.001	.04	1	<1	1.3	<1	.02	1
B 171228	1.3	33	27	42	.5	33	12	808	3.11	84	4	<2	3	45	.6	1.0	2.2	24	.27	.087	26	17	.19	53	.004	2	.77	<.001	.05	1	<1	3.1	<1	.03	<1
B 171229	.9	52	27	61	.8	58	28	1154	4.46	55	5	<2	4	26	.6	.6	1.4	20	.39	.109	27	20	.27	64	.008	<1	1.05	.002	.07	1	<1	3.5	<1	.03	1
B 171230	2.0	97	106	84	1.0	77	29	1533	5.76	105	6	<2	4	25	.8	1.0	3.4	18	.34	.142	28	20	.23	68	.007	<1	1.08	.002	.08	2	<1	4.8	1	.04	2
B 171231	.9	30	29	67	.2	28	10	331	4.35	33	2	<2	4	18	.5	<.5	.7	41	.21	.050	28	28	.34	80	.018	<1	1.18	.001	.05	2	<1	2.0	<1	.01	3
B 171232	.8	21	21	60	.3	24	11	342	3.46	27	1	<2	5	8	.3	.6	1.2	32	.08	.042	26	26	.31	136	.009	<1	1.36	.002	.11	2	<1	2.3	<1	.01	3
B 171233	.5	5	6	10	.1	4	1	45	.91	12	<1	<2	3	4	<.2	<.5	.8	16	.04	.018	34	7	.06	51	.006	1	.48	<.001	.03	1	<1	.5	<1	<.01	4
B 171234	.5	28	24	79	.1	33	10	247	4.49	33	1	<2	9	9	.5	.5	.5	33	.10	.032	30	31	.34	149	.010	1	1.48	.002	.11	2	<1	2.5	<1	<.01	3
B 171235	.7	35	29	60	.8	34	15	626	3.88	44	2	<2	4	8	.5	.7	2.0	24	.08	.071	28	23	.32	101	.006	1	1.21	.001	.08	2	<1	2.7	<1	.02	1
B 171236	.5	25	24	68	.3	29	11	337	3.81	28	1	<2	5	11	.5	<.5	<.5	32	.13	.037	28	28	.35	109	.011	<1	1.25	.002	.08	1	<1	2.0	<1	.01	3
B 171237	.8	21	21	65	.2	27	10	352	3.17	27	1	<2	5	14	.3	.6	.5	31	.19	.043	32	24	.35	109	.012	<1	1.02	.001	.08	1	<1	2.0	<1	<.01	2
B 171238	.6	29	27	63	.3	32	15	587	3.76	31	2	<2	5	16	.5	<.5	.8	30	.18	.049	31	27	.40	102	.010	<1	1.28	.002	.09	2	<1	2.9	<1	.01	2
B 171239	.5	37	23	64	.4	39	14	612	3.75	28	3	<2	4	24	.6	<.5	1.1	30	.35	.062	29	30	.45	109	.009	1	1.36	.002	.10	1	<1	2.9	<1	.02	3
B 171240	.5	44	23	55	.9	44	14	809	3.29	33	5	<2	3	45	.5	<.5	1.4	21	.71	.101	21	22	.37	104	.007	3	1.25	.004	.09	2	<1	3.0	<1	.05	2
RE B 171240	.7	43	22	53	.9	43	13	794	3.22	32	5	<2	3	44	.4	<.5	1.6	21	.70	.099	21	22	.37	102	.007	2	1.23	.003	.09	2	<1	2.9	<1	.05	2
B 171241	.7	41	29	66	.8	46	18	1060	4.23	43	4	<2	5	23	.5	<.5	1.7	26	.31	.084	27	28	.42	111	.008	2	1.50	.003	.10	2	<1	3.6	<1	.03	2
B 171242	.7	33	25	63	.4	38	17	698	4.11	31	2	<2	5	21	.4	<.5	1.3	34	.29	.054	32	33	.48	94	.011	<1	1.40	.002	.08	1	<1	2.8	<1	.01	3
B 171243	.9	29	22	54	.4	34	15	506	3.68	48	2	<2	5	10	.5	.5	1.6	23	.13	.040	35	20	.34	48	.009	<1	.95	<.001	.04	2	<1	1.9	<1	<.01	2
B 171244	.8	26	21	57	.2	32	14	503	3.76	37	2	<2	5	16	.5	<.5	1.4	28	.24	.053	27	27	.40	76	.009	1	1.16	.002	.06	2	<1	2.2	<1	.01	2
B 171245	.7	18	15	42	.1	17	8	430	3.78	34	<1	<2	7	4	.4	1.2	.7	33	.04	.065	32	16	.14	46	.022	<1	.73	<.001	.03	2	<1	1.3	1	<.01	3
B 171246	.7	28	23	69	.6	35	19	4356	3.71	28	5	<2	1	25	.4	<.5	.7	27	.34	.087	21	18	.17	166	.010	2	.94	.002	.06	1	<1	1.5	2	.03	3
B 171247	1.1	68	22	86	.7	71	32	1826	4.97	40	6	<2	3	35	.9	1.3	1.1	28	.37	.101	25	22	.21	92	.009	1	1.17	.002	.06	2	<1	3.2	1	.03	3
B 171248	.9	76	36	59	1.2	56	22	1791	4.18	36	8	<2	2	29	.9	<.5	1.4	22	.39	.112	25	22	.28	75	.011	3	1.25	.002	.07	1	<1	3.7	<1	.04	2
B 171249	1.0	26	23	51	.3	30	18	837	3.62	43	2	<2	5	13	.5	.7	1.1	18	.16	.052	28	18	.29	51	.008	1	.87	<.001	.05	3	<1	2.0	<1	.01	1
B 171250	1.3	30	53	54	.5	29	11	375	4.09	45	3	<2	3	20	.6	<.5	2.1	27	.29	.061	25	19	.23	55	.009	1	1.04	.001	.06	2	<1	1.8	<1	.02	3
B 171251	.8	32	68	65	.4	29	15	831	4.54	39	3	<2	4	20	.5	1.0	1.5	32	.27	.055	26	27	.27	83	.012	1	1.22	.002	.07	2	<1	2.1	1	.01	3
B 171252	.7	27	24	59	.2	32	12	455	3.42	32	2	<2	6	12	.5	<.5	.7	23	.15	.053	32	24	.36	101	.008	2	1.14	.002	.08	2	<1	2.7	<1	.01	2
STANDARD C3	27.3	69	38	180	5.9	38	12	821	3.48	60	25	<2	22	30	25.0	14.0	24.3	86	.62	.100	21	186	.64	164	.093	24	1.89	.038	.17	15	1	4.7	<1	.03	5
STANDARD G-2	1.8	3	3	46	<.1	8	4	571	2.13	<1	4	<2	4	75	<.2	<.5	<.5	43	.70	.109	9	86	.64	242	.136	5	.93	.075	.50	3	<1	2.7	<1	<.01	4

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Waysid Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004087 Page 1

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	%	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
351351	2.8	41	21	76	1.5	98		136	1.84	50	74	<2	1	63	1.1	<.5	.6	21	.81	.091	15	31	.22	364	.006	2	1.06	.008	.05	<1	<1	3.6	<1	.58	2
351352	3.1	28	8	466	.2	279		71	2.34	10	34	<2	4	10	2.9	.7	<.5	16	.13	.026	11	16	.22	116	.019	1	.52	.004	.05	1	<1	2.2	<1	.94	1
351353	3.1	42	20	148	.3	109		44	1.07	16	3	<2	5	16	1.8	1.2	<.5	15	.19	.052	14	17	.27	146	.013	1	.60	.005	.04	1	<1	2.6	<1	.35	1
351354	3.2	49	24	66	.5	41		44	1.07	7	4	<2	4	17	.4	1.4	<.5	17	.18	.061	16	18	.30	226	.013	1	.67	.003	.04	<1	<1	3.6	<1	.26	1
351355	.6	9	12	76	.1	26		61	1.29	2	1	<2	8	17	<.2	<.5	<.5	14	.18	.047	30	15	.34	143	.011	1	.74	.003	.03	1	<1	1.8	<1	.02	2
351356	1.3	46	28	94	.3	49		730	3.47	25	2	<2	8	25	.2	.6	<.5	25	.33	.065	25	24	.47	199	.026	1	.90	.009	.09	1	<1	3.6	<1	.02	2
351357	.5	26	17	66	.1	32		238	1.91	15	2	<2	6	32	.2	.9	<.5	14	.61	.062	21	12	.33	98	.014	<1	.54	.003	.04	1	<1	2.3	<1	.11	1
351358	.9	51	24	89	.2	46		640	3.44	27	2	<2	8	72	.2	.5	<.5	25	1.40	.063	24	23	.46	163	.022	4	1.01	.012	.14	1	<1	3.9	<1	.04	2
351359	.8	35	34	74	.2	37		699	3.33	30	2	<2	8	19	.2	1.1	.5	19	.25	.062	24	16	.25	66	.022	<1	.63	.003	.04	2	<1	2.9	<1	.02	1
351362	1.3	32	29	73	.1	41		601	3.38	26	3	<2	8	19	.2	.7	<.5	14	.37	.063	25	21	.27	76	.009	<1	.52	.003	.04	2	<1	2.8	<1	.05	1
351363	.4	41	31	74	.1	77		685	4.41	47	2	<2	8	22	<.2	.5	.5	17	.36	.078	29	18	.31	46	.012	<1	.57	.002	.04	2	<1	3.7	<1	.03	1
351364	1.3	48	37	100	.2	84		796	5.48	45	2	<2	7	30	<.2	.6	.7	34	.59	.083	23	66	.60	71	.009	<1	1.03	.004	.06	2	<1	4.8	<1	.04	2
351365	.8	55	22	63	.1	49		794	3.78	66	2	<2	11	21	<.2	1.0	.6	12	.31	.070	29	13	.23	61	.006	1	.55	.003	.07	1	<1	2.7	<1	.02	1
RE 351365	.6	57	22	62	.1	48		782	3.72	66	2	<2	11	21	.2	.7	<.5	12	.31	.067	28	13	.23	60	.005	2	.54	.004	.07	1	<1	2.7	<1	.03	1
351366	.7	42	34	81	.4	46		713	3.68	47	2	<2	10	104	<.2	<.5	.5	22	2.09	.060	24	27	.54	103	.013	2	1.09	.010	.15	1	<1	3.7	<1	.04	3
351367	.6	52	34	97	.1	44		820	4.04	28	1	<2	11	59	<.2	<.5	.5	30	1.38	.072	29	29	.66	92	.022	3	1.23	.008	.10	1	<1	4.1	<1	.02	3
351368	.6	29	27	84	.4	36		432	3.77	25	2	<2	5	17	.2	<.5	.5	30	.18	.066	31	32	.33	185	.010	<1	1.64	.007	.14	1	<1	4.2	1	.01	3
351369	.7	47	42	83	.1	48		898	4.38	55	2	<2	13	18	<.2	<.5	.8	22	.22	.051	36	22	.32	140	.012	<1	1.13	.011	.18	2	<1	4.3	1	<.01	2
351370	.7	37	33	68	.3	40		816	3.65	32	2	<2	8	12	.2	.5	.6	25	.17	.054	38	26	.32	157	.011	<1	1.22	.005	.11	2	<1	4.6	<1	<.01	2
351371	.4	46	38	90	<.1	51		793	4.10	45	1	<2	10	8	.2	<.5	<.5	32	.06	.036	36	35	.49	149	.022	<1	1.41	.008	.16	2	<1	5.0	<1	<.01	3
351372	.5	39	29	72	.1	36		624	3.88	46	1	<2	10	5	<.2	.7	<.5	22	.05	.031	35	19	.30	87	.009	<1	1.05	.005	.11	1	<1	2.8	<1	<.01	2
351373	1.2	61	30	154	.4	84		548	5.19	23	2	<2	7	12	.2	.9	.5	27	.13	.076	23	37	.35	189	.008	<1	1.90	.004	.12	2	1	3.6	<1	.02	2
351374	1.1	52	24	116	.2	66		498	3.97	20	1	<2	5	9	.2	.7	<.5	16	.10	.073	18	27	.27	84	.007	<1	1.48	<.001	.04	1	<1	2.4	<1	.01	1
351375	1.2	46	27	104	.2	56		410	5.42	22	1	<2	5	7	<.2	.5	<.5	21	.06	.088	20	31	.27	99	.008	<1	1.25	.001	.06	1	<1	2.2	<1	.02	1
351376	.8	44	41	93	.2	50		520	3.67	45	1	<2	10	5	<.2	<.5	.6	21	.04	.046	38	22	.32	91	.012	3	1.19	.004	.10	2	<1	3.2	1	<.01	2
351377	.4	38	35	83	<.1	39		586	3.84	42	1	<2	11	7	<.2	<.5	<.5	27	.05	.043	39	26	.42	84	.025	<1	1.31	.011	.13	2	<1	3.8	1	<.01	3
351378	.9	29	24	81	.2	35		224	4.17	28	1	<2	9	4	.2	.7	<.5	25	.03	.049	31	30	.34	77	.009	<1	1.58	.001	.06	2	<1	2.4	1	<.01	2
351379	.5	46	51	88	<.1	44		1012	4.32	39	1	<2	12	8	.2	<.5	<.5	27	.06	.055	38	26	.47	136	.023	<1	1.33	.007	.11	2	<1	4.9	1	<.01	3
351381	.6	29	24	91	.2	37		318	4.09	31	1	<2	7	7	<.2	<.5	<.5	28	.09	.063	35	29	.46	91	.013	<1	1.42	.003	.07	1	<1	2.6	<1	<.01	3
351382	.6	63	8	110	.1	46		654	4.41	38	1	<2	9	3	<.2	.6	<.5	4	.02	.046	44	7	.08	43	.003	<1	.40	.002	.05	1	<1	1.6	<1	<.01	<1
351383	<.2	20	4	33	<.1	42		594	2.90	14	1	<2	11	4	<.2	<.5	<.5	2	.02	.020	52	4	.04	44	.002	<1	.24	.001	.05	1	<1	1.2	1	<.01	<1
351384	<.2	32	16	105	.1	39		798	3.98	15	1	<2	8	8	<.2	<.5	<.5	13	.10	.043	32	19	.41	105	.005	<1	1.12	.006	.08	1	<1	2.1	1	<.01	2
351385	57.8	108	393	61	.5	39		783	5.00	48	3	<2	7	13	.2	.9	3.8	9	.13	.061	29	9	.09	91	.003	<1	.53	<.001	.05	2	<1	3.0	<1	.02	<1
351386	.7	41	114	81	.3	39		777	4.06	32	4	<2	5	20	<.2	<.5	1.0	21	.28	.066	28	24	.30	226	.008	<1	1.11	.002	.09	1	<1	3.6	<1	.02	2
STANDARD C3	26.8	64	35	169	5.3	35		795	3.37	59	24	2	21	30	22.6	16.5	22.3	81	.60	.095	22	178	.63	161	.087	20	1.78	.043	.17	15	2	4.8	<1	.03	6
STANDARD G-2	1.6	3	4	43	<.1	7		528	1.96	1	3	<2	5	82	<.2	<.5	<.5	38	.67	.097	10	78	.60	240	.121	1	1.00	.134	.52	2	<1	2.7	<1	<.01	4

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
- SAMPLE TYPE: SOIL SS80 60 Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 17 2000 DATE REPORT MAILED: Oct 25/00 SIGNED BY. C. Leong .D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	[illegible]	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
351387	.3	23	35	54	.1	25	[illegible]	574	3.06	28	1	<2	9	11	<.2	.8	<.5	16	.16	.053	38	14	.26	89	.008	2	.74	.003	.07	2	<1	2.1	<1	<.01	2
351388	.4	49	36	77	.1	47	[illegible]	921	4.44	50	1	<2	16	13	<.2	.8	<.5	20	.15	.056	46	22	.36	99	.006	5	1.12	.006	.11	2	<1	4.4	<1	<.01	2
351389	2.8	34	25	32	.1	28	[illegible]	197	2.84	66	2	<2	13	7	<.2	.8	1.0	8	.08	.031	37	9	.14	43	.003	<1	.47	<.001	.04	2	<1	2.4	<1	<.01	1
351701	.4	43	28	83	.1	40	[illegible]	687	3.68	32	2	<2	10	114	<.2	<.5	.5	26	2.24	.062	25	22	.58	111	.014	5	1.09	.008	.11	1	<1	3.9	<1	.04	3
351702	1.2	44	44	80	.3	44	[illegible]	1146	4.34	52	1	<2	14	20	<.2	.7	1.3	23	.28	.061	34	17	.32	82	.006	4	.84	.004	.11	2	<1	3.8	<1	.02	2
351703	.4	27	26	59	<.1	30	[illegible]	485	3.04	26	1	<2	9	11	<.2	1.0	<.5	21	.15	.030	34	21	.35	89	.015	2	.91	.003	.07	2	<1	3.1	<1	<.01	2
351704	.4	42	51	69	.1	41	[illegible]	1046	3.99	49	2	<2	11	16	<.2	1.4	1.0	21	.23	.063	39	18	.30	95	.006	<1	.96	.003	.10	2	<1	3.9	1	<.01	2
351705	.5	30	41	62	<.1	34	[illegible]	520	3.52	44	1	<2	9	14	.2	.7	.7	21	.20	.048	38	20	.31	82	.004	1	1.08	.003	.07	3	<1	2.3	<1	<.01	2
351706	.6	32	39	66	.4	32	[illegible]	626	3.63	45	2	<2	8	14	.2	.9	.8	21	.22	.032	35	17	.29	71	.004	1	.92	.003	.06	2	<1	2.8	<1	<.01	2
351707	.6	40	31	68	.1	37	[illegible]	683	3.85	51	1	<2	11	10	<.2	.8	<.5	25	.14	.037	39	18	.34	76	.006	2	1.01	.004	.08	2	<1	3.3	<1	<.01	2
351708	.7	35	91	62	.1	31	[illegible]	577	3.49	49	1	<2	10	9	<.2	1.5	3.6	16	.11	.031	42	15	.26	57	.004	1	.81	.002	.06	2	<1	2.2	<1	<.01	1
351709	.2	37	31	77	.1	40	[illegible]	702	3.93	27	2	<2	10	12	<.2	1.2	<.5	30	.19	.050	40	26	.49	71	.013	<1	1.24	.003	.06	2	<1	3.7	<1	<.01	3
351710	.2	31	35	66	<.1	34	[illegible]	699	3.45	29	2	<2	11	10	<.2	.9	<.5	16	.11	.038	33	16	.26	84	.008	1	.85	.002	.10	2	<1	2.5	<1	.01	2
RE 351710	.4	31	35	67	<.1	34	[illegible]	703	3.45	30	2	<2	12	10	<.2	1.3	<.5	16	.11	.038	33	17	.27	87	.008	3	.86	.003	.10	2	<1	2.6	<1	.01	2
351711	.3	20	53	65	.1	24	[illegible]	269	3.36	26	1	<2	7	10	<.2	<.5	.5	21	.15	.039	30	17	.22	62	.004	2	1.06	.001	.05	2	<1	1.8	<1	<.01	2
351712	.3	26	51	75	.3	31	[illegible]	539	4.10	40	1	<2	8	12	<.2	.9	<.5	30	.15	.055	35	21	.27	75	.008	<1	1.11	.002	.07	2	<1	2.5	<1	<.01	2
351713	.8	39	40	77	.4	53	[illegible]	366	4.11	26	2	<2	10	11	<.2	.6	.6	30	.11	.056	29	26	.27	99	.017	1	1.39	.003	.07	2	<1	3.0	<1	.01	2
351714	.8	31	34	80	.1	31	[illegible]	286	3.95	42	1	<2	10	5	<.2	.6	.5	21	.04	.041	36	20	.26	60	.007	<1	1.15	.001	.04	2	<1	2.1	<1	<.01	2
351715	1.0	38	31	93	.1	41	[illegible]	433	4.23	31	1	<2	9	7	<.2	1.3	.5	35	.08	.047	37	33	.50	61	.011	<1	1.56	.003	.05	2	<1	2.8	<1	<.01	3
351716	.5	41	42	80	.2	42	[illegible]	1081	4.10	43	1	<2	10	7	<.2	.8	<.5	30	.06	.036	40	24	.47	67	.007	<1	1.41	.002	.06	3	<1	3.5	<1	<.01	3
351717	<.2	35	49	75	.3	38	[illegible]	658	3.55	45	2	<2	10	11	<.2	.9	.5	21	.15	.042	36	19	.36	96	.006	<1	1.03	.002	.06	2	<1	4.0	<1	<.01	2
351718	.3	40	69	72	.1	43	[illegible]	666	3.99	48	1	<2	8	9	<.2	.8	<.5	26	.11	.041	34	26	.37	100	.006	<1	1.30	.003	.08	4	<1	3.1	<1	<.01	2
351719	.6	34	33	80	.1	41	[illegible]	515	3.24	26	1	<2	7	13	<.2	.6	<.5	21	.17	.054	32	24	.33	126	.009	<1	1.04	.003	.07	1	<1	2.4	<1	<.01	2
351720	1.3	47	28	113	.2	63	[illegible]	402	4.93	25	2	<2	5	16	<.2	1.0	<.5	30	.21	.057	26	39	.40	218	.007	<1	1.58	.003	.09	1	<1	2.9	<1	.01	3
351721	.3	46	35	81	.1	45	[illegible]	1084	4.24	48	2	<2	12	15	<.2	.8	.5	26	.22	.066	37	23	.41	120	.012	4	1.11	.005	.11	2	<1	4.3	<1	<.01	2
351722	1.2	48	36	91	.3	51	[illegible]	698	3.53	35	2	<2	9	27	<.2	1.2	.6	19	.51	.062	24	22	.44	150	.016	1	.81	.004	.06	2	<1	3.3	<1	.02	2
351723	.5	39	31	80	.1	38	[illegible]	687	3.60	35	1	<2	10	55	<.2	.9	.5	22	1.04	.070	30	19	.47	82	.014	2	.87	.004	.07	1	<1	3.4	<1	.02	2
351724	.6	41	29	80	.1	38	[illegible]	697	3.53	29	2	<2	10	86	<.2	<.5	<.5	22	1.70	.070	28	20	.50	98	.019	6	.89	.006	.07	2	<1	3.7	<1	.02	2
351725	.5	40	30	79	.2	39	[illegible]	791	3.50	29	2	<2	10	23	<.2	.8	<.5	24	.36	.070	30	19	.42	92	.018	2	.80	.005	.05	1	<1	3.4	<1	.02	2
351727	1.5	38	30	83	.4	43	[illegible]	601	3.30	21	3	<2	7	16	<.2	1.3	<.5	21	.21	.057	27	19	.29	153	.012	4	.70	.002	.04	3	<1	2.5	<1	.02	1
351729	1.8	31	12	73	.1	36	[illegible]	442	2.83	12	1	<2	8	6	<.2	1.1	<.5	15	.05	.039	27	20	.20	80	.012	<1	.53	.001	.03	2	<1	1.9	<1	<.01	1
351730	1.6	45	22	98	.3	54	[illegible]	676	3.46	15	2	<2	8	20	<.2	.8	<.5	26	.25	.068	26	26	.42	204	.022	3	.92	.004	.06	1	<1	3.3	<1	.02	2
351731	.8	33	17	76	.2	40	[illegible]	660	2.81	14	2	<2	7	20	<.2	.9	<.5	17	.23	.066	24	14	.35	121	.013	<1	.54	.002	.04	1	<1	2.3	<1	<.01	1
351732	2.9	53	39	129	1.7	55	[illegible]	379	3.33	17	6	<2	4	24	.2	1.9	<.5	46	.25	.101	29	38	.37	450	.010	2	1.97	.005	.16	1	<1	5.0	<1	.02	4
STANDARD C3	27.9	67	38	175	5.5	37	[illegible]	810	3.40	60	24	3	22	30	23.6	17.5	24.1	83	.61	.096	22	186	.64	167	.088	25	1.89	.042	.17	15	1	5.0	<1	.03	7
STANDARD G-2	1.6	3	3	46	<.1	8	[illegible]	558	2.09	<1	3	<2	4	77	<.2	<.5	<.5	42	.69	.100	11	83	.63	242	.131	<1	.98	.088	.50	3	<1	2.9	<1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Date 1 FA ____

SAMPLE#	Au** ppb
B 171219	58
B 171220	32
B 171221	60
B 171222	35
B 171223	38
B 171224	70
B 171225	10
B 171226	66
B 171227	21
B 171228	68
B 171229	60
B 171230	160
B 171231	29
B 171232	24
B 171233	73
B 171234	22
B 171235	76
B 171236	27
B 171237	46
B 171238	32
B 171239	18
B 171240	27
RE B 171243	209
B 171241	119
B 171242	28
B 171243	168
B 171244	30
B 171245	64
B 171246	28
B 171247	29
B 171248	137
B 171249	136
B 171250	134
B 171251	35
B 171252	60
STANDARD AU-S	49

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
351733	1.8	32	32	101	1.0	35	9	155	2.63	25	2	<2	4	17	<.2	1.2	<.5	31	.18	.081	29	24	.26	303	.006	3	1.25	.007	.11	1	<1	3.2	<1	.01	2
351734	1.7	26	24	97	.5	34	13	197	2.62	20	2	<2	6	17	<.2	1.0	<.5	26	.18	.063	31	25	.29	258	.007	2	1.16	.006	.11	2	<1	2.9	<1	<.01	3
351735	1.2	24	15	67	.2	23	9	444	2.40	16	1	<2	4	12	<.2	.7	<.5	18	.10	.040	30	20	.26	186	.008	<1	.88	.004	.08	1	<1	2.1	<1	<.01	2
351736	1.0	26	18	74	.2	26	11	373	2.69	19	1	<2	3	11	<.2	.6	<.5	22	.11	.046	33	21	.29	218	.007	3	1.06	.004	.10	2	<1	2.5	<1	<.01	2
351737	.4	41	28	81	.1	37	17	819	3.79	38	1	<2	9	12	<.2	.5	<.5	19	.11	.040	39	19	.28	218	.007	<1	1.02	.005	.12	2	<1	3.8	<1	<.01	2
351738	1.4	25	24	66	.2	25	11	443	3.06	24	1	<2	3	14	<.2	1.0	<.5	26	.12	.049	32	23	.32	215	.007	<1	1.05	.004	.09	2	<1	2.0	<1	<.01	2
351739	1.7	27	20	66	.9	25	9	340	3.52	25	1	<2	4	8	<.2	1.1	<.5	26	.06	.058	29	24	.29	135	.010	<1	.93	.003	.07	2	<1	1.8	<1	.01	2
351740	1.8	15	17	38	.5	15	4	207	2.65	10	1	<2	1	10	<.2	.7	<.5	22	.07	.072	22	18	.17	139	.008	2	.74	.002	.06	1	<1	1.0	<1	.02	2
351741	2.2	18	18	38	.9	14	5	227	2.80	18	1	<2	4	8	<.2	1.0	<.5	30	.04	.078	26	20	.16	101	.012	1	.78	.002	.06	1	<1	1.3	<1	.01	2
351742	1.8	17	17	39	.3	13	5	436	2.79	11	1	<2	2	7	<.2	.9	<.5	30	.03	.056	24	15	.10	114	.022	<1	.59	.002	.04	2	<1	1.2	<1	.01	3
351743	2.1	38	23	77	.5	32	10	423	3.09	17	2	<2	5	9	<.2	1.3	<.5	30	.06	.051	28	26	.29	152	.018	1	1.10	.003	.08	2	<1	2.7	<1	<.01	2
351744	1.5	19	17	40	.4	14	4	134	2.86	13	1	<2	3	8	<.2	1.1	<.5	30	.03	.050	23	22	.17	103	.010	<1	.93	.002	.05	1	<1	1.4	<1	.01	2
351745	.9	10	15	23	.9	7	1	67	1.69	5	<1	<2	2	5	<.2	<.5	<.5	21	.02	.039	22	15	.09	123	.008	1	.71	.001	.03	1	<1	1.0	1	<.01	3
351746	1.9	15	14	33	1.5	13	2	77	2.04	9	1	<2	2	5	<.2	.7	<.5	29	.02	.047	22	15	.10	111	.010	<1	.63	.001	.04	1	<1	1.0	<1	.01	2
351747	2.3	19	15	42	1.5	17	3	104	3.21	14	1	<2	2	8	<.2	1.4	<.5	30	.03	.179	21	24	.16	122	.010	2	.85	.002	.06	1	<1	1.0	<1	.02	2
351748	1.2	7	10	15	.3	5	1	56	1.47	4	<1	<2	2	4	<.2	<.5	<.5	21	.02	.048	22	11	.07	118	.009	<1	.50	<.001	.03	1	<1	.6	<1	<.01	2
351749	.8	27	19	78	.8	34	8	170	3.27	8	2	<2	3	15	<.2	<.5	<.5	26	.23	.055	22	55	.17	346	.004	<1	1.14	.002	.03	1	<1	2.2	<1	.02	3
351750	1.1	30	18	83	.5	32	8	178	4.09	10	2	<2	3	12	<.2	<.5	<.5	22	.17	.050	27	34	.23	238	.005	<1	1.06	.002	.03	1	<1	2.9	<1	.01	2
351851	.3	48	33	83	.2	41	19	774	3.74	32	2	<2	11	77	<.2	<.5	.5	27	1.49	.071	30	21	.52	85	.016	5	.92	.006	.07	2	<1	3.7	<1	.02	2
351852	.5	41	28	79	.2	39	17	718	3.63	40	2	<2	11	130	<.2	<.5	.7	23	2.39	.060	24	19	.45	85	.007	4	.92	.006	.11	1	<1	3.6	<1	.04	2
351853	1.0	15	15	41	.2	18	4	126	2.45	17	1	<2	5	12	<.2	<.5	<.5	23	.17	.027	34	20	.19	91	.005	<1	.82	.002	.04	1	<1	1.4	<1	<.01	3
351854	.5	20	22	56	.2	27	8	231	3.11	26	1	<2	6	14	<.2	<.5	<.5	22	.20	.044	31	24	.32	109	.006	<1	.99	.003	.06	1	<1	2.0	<1	<.01	2
351855	.3	31	46	68	.5	40	14	635	3.65	39	2	<2	5	18	<.2	<.5	.5	25	.28	.060	30	25	.35	155	.005	<1	1.16	.003	.07	2	<1	3.5	<1	.02	2
RE 351855	.3	31	46	67	.5	40	14	640	3.61	39	2	<2	5	18	<.2	.7	.6	22	.28	.059	30	25	.34	153	.004	1	1.14	.003	.07	2	<1	3.4	<1	.02	2
351856	.3	36	71	76	1.0	49	17	725	4.15	39	2	<2	7	13	<.2	.7	.7	24	.17	.054	35	29	.39	152	.005	<1	1.41	.003	.08	2	<1	4.6	<1	.01	3
351857	.3	22	27	57	.1	27	9	194	3.41	37	1	<2	7	6	<.2	<.5	<.5	22	.07	.027	34	22	.25	83	.003	<1	.94	.002	.04	2	<1	1.6	1	<.01	2
351858	.4	27	32	65	.1	35	13	214	3.10	37	1	<2	9	9	<.2	<.5	<.5	18	.12	.042	37	23	.30	119	.005	<1	.93	.002	.06	2	<1	2.4	<1	<.01	2
351859	.7	37	40	72	.1	44	19	637	4.01	51	1	<2	9	10	<.2	.9	.7	16	.13	.059	40	25	.26	127	.004	<1	1.04	.002	.06	2	<1	2.8	<1	<.01	2
351860	.4	28	23	72	.1	36	9	216	3.58	24	1	<2	7	8	<.2	<.5	<.5	26	.08	.038	30	28	.31	98	.010	<1	1.19	.003	.06	1	<1	2.0	<1	<.01	2
351861	.4	17	16	47	<.1	17	5	114	2.83	27	1	<2	7	4	<.2	<.5	<.5	23	.03	.039	30	18	.14	68	.009	2	.83	.001	.03	1	<1	1.4	<1	<.01	2
351862	<.2	21	24	59	.1	24	8	190	3.95	32	1	<2	5	8	<.2	<.5	<.5	26	.09	.043	28	25	.25	116	.006	<1	1.08	.003	.05	2	<1	1.7	<1	<.01	2
351863	1.0	24	24	73	.2	35	13	381	3.76	31	1	<2	6	8	<.2	.6	<.5	31	.10	.039	37	34	.44	100	.005	1	1.29	.003	.05	2	<1	2.2	1	<.01	3
351864	.6	30	51	87	.5	42	15	115	3.96	26	2	<2	6	15	<.2	<.5	.6	31	.20	.056	32	33	.40	125	.004	<1	1.56	.004	.07	2	<1	3.4	1	.01	3
351865	.4	12	18	42	<.1	16	6	282	2.44	24	<1	<2	5	6	<.2	.8	.7	31	.06	.024	37	14	.08	83	.008	<1	.67	.002	.04	2	<1	1.3	1	<.01	3
STANDARD C3	28.3	69	36	173	5.7	37	12	816	3.46	60	25	3	23	30	23.6	17.8	23.6	87	.62	.099	22	185	.64	167	.088	21	1.81	.041	.17	16	1	4.8	<1	.03	7
STANDARD G-2	1.5	3	2	45	<.1	7	4	546	2.02	<1	3	<2	4	74	<.2	<.5	<.5	39	.66	.101	10	79	.62	234	.127	1	.90	.087	.49	3	<1	2.8	1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
351867	.3	25	38	61	.4	35	12	475	3.29	27	1	<2	6	12	<.2	<.5	.6	16	.17	.058	31	21	.29	72	.007	1	1.06	.008	.07	2	<1	2.6	<1	<.01	2
351868	.4	23	37	59	.4	28	12	387	3.34	26	1	<2	6	11	<.2	.9	.5	18	.15	.037	30	18	.24	74	.005	2	.98	.005	.07	2	<1	1.8	<1	<.01	2
351870	.3	36	46	71	.5	38	16	653	4.22	43	2	<2	7	18	<.2	.6	1.3	27	.26	.059	35	29	.36	91	.004	<1	1.46	.006	.10	2	<1	4.1	<1	.01	3
351871	.2	28	51	76	.1	36	17	522	3.69	49	1	<2	7	10	<.2	.5	.7	23	.13	.047	34	27	.41	72	.007	<1	1.17	.005	.07	2	<1	2.7	<1	<.01	2
351872	.4	17	21	55	.1	17	6	163	3.28	27	1	<2	8	4	<.2	<.5	<.5	24	.03	.035	32	20	.19	61	.005	1	.97	.003	.05	2	<1	1.5	<1	<.01	2
351873	2.2	15	15	43	.1	13	4	250	3.73	15	1	<2	5	7	<.2	1.0	<.5	32	.03	.101	26	24	.20	100	.011	<1	1.07	.002	.05	2	<1	1.4	<1	<.01	3
351874	1.7	25	21	68	.3	25	6	217	3.91	15	1	<2	4	8	<.2	1.4	<.5	29	.05	.077	20	34	.25	136	.014	<1	1.59	.004	.05	2	<1	2.3	<1	.02	2
351875	2.4	21	15	57	.4	20	5	167	3.06	13	1	<2	3	7	<.2	1.0	<.5	20	.05	.084	20	22	.15	92	.010	<1	1.04	.002	.03	1	<1	1.5	<1	.01	2
351877	6.8	45	21	109	.8	42	13	485	4.06	30	4	<2	6	12	<.2	3.3	<.5	35	.08	.105	25	25	.28	286	.020	<1	1.16	.004	.07	1	<1	2.9	<1	<.01	2
351878	2.3	18	15	92	2.7	26	5	127	2.18	13	4	<2	1	12	<.2	1.7	<.5	25	.08	.080	24	19	.25	328	.007	<1	.93	.004	.08	1	<1	1.6	<1	.01	2
351879	1.5	37	18	88	.3	34	12	420	3.22	17	2	<2	10	8	<.2	1.9	<.5	21	.04	.046	32	22	.37	197	.010	1	1.10	.003	.09	1	<1	2.6	1	<.01	2
351880	.9	49	35	109	.1	51	18	815	4.28	23	2	<2	10	11	<.2	1.4	.5	32	.09	.062	35	30	.49	281	.022	<1	1.50	.005	.11	1	<1	4.8	1	<.01	3
RE 351880	.9	48	35	108	.1	50	18	795	4.17	22	2	<2	11	9	<.2	1.0	<.5	32	.09	.061	34	30	.49	276	.022	<1	1.47	.009	.11	2	<1	4.7	1	<.01	3
351881	2.6	35	38	94	.3	36	22	937	4.76	38	3	<2	3	11	<.2	2.2	<.5	35	.10	.090	23	29	.32	213	.012	<1	1.29	.003	.09	2	<1	2.2	1	.01	3
351882	1.4	29	21	79	.3	30	14	564	3.15	32	2	<2	6	8	<.2	1.5	<.5	21	.06	.041	32	19	.28	149	.011	<1	.83	.003	.05	2	<1	2.1	2	<.01	2
351883	.8	38	31	91	.1	39	17	818	3.70	32	2	<2	8	12	<.2	1.0	<.5	21	.10	.043	35	22	.34	255	.012	1	1.10	.005	.10	2	<1	3.3	1	<.01	2
351884	2.4	33	25	130	.5	51	20	876	4.09	24	4	<2	2	13	<.2	1.3	<.5	29	.11	.082	23	36	.34	335	.006	<1	1.44	.005	.10	2	<1	2.7	1	.01	3
351885	.4	42	30	82	.1	40	18	829	3.84	40	2	<2	11	19	<.2	.7	<.5	21	.21	.059	36	21	.33	197	.011	1	1.05	.008	.13	2	<1	3.9	<1	<.01	2
351886	.4	56	27	108	.2	52	21	828	4.24	16	2	<2	9	21	<.2	1.1	.6	33	.25	.071	28	32	.52	181	.028	<1	1.26	.006	.08	1	<1	4.9	<1	<.01	3
351887	.4	47	35	97	.2	44	21	799	4.16	37	2	<2	11	20	<.2	.8	.7	25	.24	.070	37	26	.42	217	.015	1	1.20	.008	.13	2	<1	4.4	<1	<.01	3
351889	.8	41	26	97	.3	46	17	774	3.50	18	4	<2	9	18	.2	1.1	<.5	22	.16	.064	29	21	.29	136	.027	1	.81	.005	.05	1	<1	3.2	<1	<.01	2
351890	.5	43	22	230	.1	103	19	1525	3.91	14	6	<2	12	11	1.1	<.5	<.5	7	.10	.060	32	5	.11	91	.001	1	.59	.003	.04	1	<1	1.5	1	<.01	<1
351891	1.1	68	40	156	.1	91	57	1945	3.74	16	7	<2	9	10	.6	.7	.5	22	.04	.056	24	21	.32	169	.028	<1	1.28	.003	.06	2	<1	3.6	2	<.01	2
351892	.3	39	27	111	.1	60	25	1644	3.89	14	4	<2	13	8	.4	.6	<.5	5	.05	.063	37	6	.06	128	.002	<1	.41	.001	.04	2	<1	1.9	1	<.01	<1
351893	.3	36	19	96	.1	62	20	1087	3.39	12	3	<2	11	7	.3	<.5	<.5	7	.05	.047	30	15	.14	88	.004	<1	.43	.004	.03	1	<1	1.8	1	<.01	1
351895	.9	41	26	86	.2	45	17	544	3.50	22	2	<2	7	22	.2	1.2	<.5	26	.33	.065	22	24	.39	138	.030	<1	.85	.008	.05	1	<1	3.2	<1	.01	2
351897	.5	36	31	70	.2	36	15	727	3.28	31	1	<2	8	15	<.2	1.1	.5	19	.22	.068	26	14	.28	68	.021	<1	.54	.005	.03	3	<1	2.5	<1	.02	1
351898	.6	38	28	77	.1	38	16	619	3.29	26	2	<2	8	95	.2	<.5	.6	24	1.82	.078	24	18	.46	103	.021	5	.75	.006	.05	1	<1	3.1	<1	.04	2
351899	.7	41	18	85	.1	47	16	571	3.11	14	2	<2	7	37	.2	.6	<.5	31	.50	.071	23	27	.49	151	.051	2	.99	.015	.07	1	<1	3.5	<1	<.01	3
351900	.4	33	29	83	.2	36	16	400	3.29	26	2	<2	9	27	<.2	<.5	.9	19	.45	.076	32	22	.47	115	.012	<1	1.01	.006	.07	1	<1	3.0	<1	.02	2
351901	.6	23	23	74	1.0	29	6	147	1.71	11	2	<2	2	19	<.2	<.5	<.5	17	.22	.061	25	21	.29	424	.006	<1	1.09	.004	.09	1	<1	2.2	<1	.03	2
351902	1.1	23	24	66	1.2	27	11	264	2.00	19	3	<2	2	24	.2	.6	<.5	21	.30	.073	23	22	.28	443	.005	<1	1.09	.005	.08	1	<1	2.2	<1	.04	2
351903	1.6	36	24	72	.4	36	16	390	2.74	17	3	<2	4	19	.2	.8	<.5	24	.20	.062	24	20	.28	321	.010	4	.88	.005	.05	1	<1	2.6	<1	.03	2
351904	1.4	42	23	105	.6	63	18	692	2.58	15	4	<2	5	17	.3	1.0	<.5	28	.17	.069	24	25	.31	239	.028	<1	1.04	.005	.06	1	<1	3.2	<1	.02	2
STANDARD C3	27.3	64	35	169	5.3	36	11	791	3.30	58	24	3	22	29	23.2	18.2	24.0	81	.59	.095	22	178	.61	162	.085	20	1.83	.041	.17	15	1	4.7	<1	.03	7
STANDARD G-2	1.7	3	3	46	<.1	8	4	564	2.08	<1	3	<2	4	78	<.2	<.5	<.5	40	.69	.105	11	83	.63	248	.128	<1	1.00	.099	.52	2	<1	2.8	1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Au** ppb
B 171253	17
B 171254	20
B 171255	43
B 171256	41
B 171257	57
B 171258	69
B 171259	203
B 171260	56
B 171261	76
B 171262	151
B 171263	115
B 171264	25
B 171265	22
B 171266	563
B 171267	38
B 171268	60
B 171269	81
B 171270	57
RE B 171270	112
B 171271	69
B 171272	88
B 171273	133
B 171274	28
B 171275	42
B 171276	14
B 171277	41
B 171278	51
B 171279	66
B 171280	167
B 171281	18
B 171282	66
B 171283	68
B 171284	36
B 171285	41
B 171286	98
STANDARD AU-S	47

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA

SAMPLE#	Au** ppb
B 171287	165
B 171288	74
B 171289	93
B 171290	40
B 171291	158
B 171292	90
B 171293	40
B 171294	56
B 171295	44
B 171296	41
B 171297	40
B 171298	79
B 171299	43
B 171300	21
RE B 171300	20
B 171301	134
B 171302	148
B 171303	75
B 171304	85
B 171305	35
B 171306	31
B 171307	85
B 171308	303
B 171519	147
B 171520	96
B 171521	25
B 171522	29
B 171523	59
B 171524	80
B 171525	99
B 171526	134
B 171527	132
B 171528	304
B 171529	498
B 171530	128
STANDARD AU-S	49

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ____

SAMPLE#	Au** ppb
B 171531	265
B 171532	520
B 171533	62
B 171534	22
B 171535	156
B 171536	69
B 171537	84
B 171538	45
B 171539	46
B 171540	115
B 171541	156
B 171542	35
B 171543	44
B 171544	72
B 171545	33
RE B 171545	17
B 171546	117
B 171547	11
B 171548	242
B 171549	67
B 171550	438
STANDARD AU-S	47

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003152R Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 171151	.9	25	20	55	.2	20	8	269	3.79	76	1	<2	4	7	.5	.5	2.0	31	.04	.076	26	15	.10	43	.012	<1	.70	.003	.05	3	<1	1.2	1	<.01	3
B 171152	.7	25	16	37	.2	17	5	127	3.35	70	1	<2	4	7	.4	.6	1.2	31	.03	.063	27	14	.06	54	.013	<1	.58	.002	.03	2	<1	1.1	2	<.01	2
B 171153	1.0	28	19	61	.2	26	16	545	3.43	37	1	<2	2	17	.3	<.5	<.5	24	.21	.073	22	16	.18	78	.006	<1	.86	.004	.06	2	<1	1.3	1	.01	3
B 171154	1.0	36	21	76	.2	37	16	725	3.79	34	2	<2	6	16	.5	<.5	<.5	26	.20	.075	26	24	.39	74	.006	<1	1.31	.004	.08	2	<1	3.1	<1	.01	3
B 171155	1.5	33	25	65	.2	35	15	547	3.70	44	2	<2	6	14	.4	.8	1.2	23	.18	.065	26	23	.40	55	.006	<1	1.17	.004	.06	3	<1	2.7	<1	<.01	3
B 171156	1.5	26	13	61	.2	31	13	412	3.44	24	1	<2	6	11	.3	.6	<.5	25	.14	.051	27	24	.49	47	.007	<1	1.24	.004	.05	1	<1	2.4	<1	<.01	3
B 171157	2.9	42	22	70	.5	41	18	783	4.32	50	3	<2	4	13	.5	.9	<.5	23	.15	.063	24	21	.26	68	.007	<1	1.06	.003	.07	2	<1	2.6	1	.02	3
B 171158	.6	28	15	60	<.1	29	9	292	2.72	17	1	<2	9	7	<.2	.7	<.5	19	.07	.040	38	20	.31	57	.016	<1	.92	.003	.05	1	<1	2.1	<1	<.01	2
B 171159	.3	10	13	24	.5	8	3	117	1.88	15	<1	<2	1	5	<.2	<.5	<.5	22	.04	.039	25	14	.16	79	.009	<1	.87	.003	.05	1	<1	.9	1	<.01	3
B 171160	.5	28	35	60	.4	25	10	302	3.44	35	1	<2	4	8	.3	.8	<.5	29	.11	.062	27	24	.29	99	.012	<1	1.22	.004	.08	2	<1	2.1	<1	.01	3
B 171161	.7	27	64	52	.4	18	6	177	3.85	27	1	<2	3	9	.5	<.5	<.5	31	.11	.055	22	24	.26	106	.009	<1	1.23	.004	.08	2	<1	1.5	<1	.02	4
B 171162	.2	12	12	31	.2	11	4	114	1.75	13	<1	<2	1	7	<.2	<.5	<.5	23	.06	.036	26	13	.14	88	.010	<1	.71	.002	.06	1	<1	.9	<1	<.01	3
B 171163	.6	22	18	61	.2	26	10	335	3.11	27	1	<2	4	11	.4	<.5	<.5	31	.13	.040	26	24	.35	95	.014	<1	1.04	.004	.08	1	<1	1.9	<1	<.01	3
B 171164	.7	47	36	71	1.2	39	19	1354	4.42	47	2	<2	2	29	.6	1.1	<.5	40	.41	.113	20	32	.40	174	.008	<1	1.67	.006	.13	2	<1	3.3	<1	.04	5
B 171165	.8	62	38	66	.7	49	19	1290	4.35	110	3	<2	5	27	.6	1.0	.6	33	.28	.109	24	30	.41	132	.006	<1	1.74	.006	.11	2	<1	5.1	<1	.03	4
B 171166	.5	25	19	54	.1	21	8	211	4.35	39	1	<2	8	5	.5	.7	<.5	34	.06	.046	29	25	.29	75	.011	<1	1.16	.002	.05	2	<1	1.9	1	.01	4
B 171167	.3	11	6	35	.2	11	7	266	2.21	18	1	<2	1	6	.2	.7	<.5	19	.08	.056	20	10	.05	67	.006	<1	.57	.003	.04	1	<1	.9	<1	.01	3
B 171168	.6	32	19	91	.6	37	19	854	4.93	56	2	<2	4	19	.6	.8	1.5	34	.21	.088	20	29	.35	121	.009	<1	1.71	.005	.08	2	<1	2.7	<1	.02	6
B 171169	.9	42	20	87	.7	40	22	1289	5.05	89	3	<2	2	21	.6	.5	1.5	29	.21	.103	19	28	.30	108	.008	<1	1.43	.004	.08	3	<1	2.4	<1	.02	6
B 171170	1.3	20	16	43	.1	21	8	302	3.06	86	1	<2	3	7	.4	.5	.8	24	.06	.060	25	10	.04	32	.008	<1	.50	.002	.03	2	<1	1.1	2	.01	3
RE B 171170	1.3	20	17	44	.1	22	8	311	3.09	88	1	<2	3	7	.4	.6	.8	26	.06	.061	25	11	.04	32	.008	<1	.50	.003	.03	3	<1	1.1	1	.01	3
B 171171	2.0	53	34	102	.7	49	28	1479	5.30	120	4	<2	3	20	.9	.8	2.1	26	.19	.120	21	24	.21	90	.008	<1	1.33	.004	.08	3	<1	3.4	1	.03	6
B 171172	1.7	46	27	65	.6	44	21	1384	4.55	73	3	<2	6	20	.6	.6	4.1	25	.20	.090	27	23	.27	98	.005	<1	1.53	.004	.09	2	<1	4.1	1	.01	5
B 171173	1.6	26	18	53	.4	26	10	315	4.66	107	1	2	2	9	.5	.6	<.5	28	.09	.065	25	14	.10	57	.011	<1	.58	.002	.04	3	<1	1.0	2	.01	4
B 171174	1.2	25	24	70	.2	25	10	322	5.13	48	1	<2	3	12	.5	.6	<.5	25	.13	.093	21	21	.22	97	.008	<1	1.03	.003	.05	3	<1	1.3	<1	.02	5
B 171175	.9	32	24	76	.4	25	12	389	4.15	35	2	<2	3	21	.6	.5	<.5	31	.19	.107	20	22	.19	111	.007	<1	1.23	.004	.07	1	<1	1.9	1	.02	4
B 171176	1.5	32	18	65	.2	32	13	341	3.85	51	2	<2	3	12	.6	.7	<.5	22	.14	.066	23	17	.24	61	.006	<1	1.04	.003	.06	2	<1	1.7	<1	.01	3
B 171177	.8	22	19	52	.5	22	16	613	3.06	27	1	<2	2	9	.4	.7	<.5	25	.10	.061	22	23	.27	122	.007	<1	1.14	.004	.10	2	<1	1.6	<1	.02	4
B 171178	.7	29	21	64	.2	25	12	693	3.53	35	1	<2	2	8	.5	.8	<.5	28	.06	.083	21	24	.27	140	.008	<1	1.26	.004	.11	2	<1	2.1	<1	.02	4
B 171179	.6	31	24	61	.7	25	13	759	3.21	36	1	<2	2	17	.5	.9	.5	26	.23	.085	22	22	.31	140	.007	<1	1.18	.003	.09	2	<1	2.1	<1	.02	4
B 171180	.5	31	19	60	.5	28	14	638	3.45	36	1	<2	5	10	.5	.5	<.5	28	.11	.054	26	24	.37	89	.011	<1	1.18	.004	.08	2	<1	2.6	1	<.01	4
B 171181	.4	24	17	49	.2	18	7	216	2.63	25	1	<2	2	9	.4	<.5	<.5	32	.11	.050	25	19	.22	128	.010	<1	1.00	.003	.06	1	<1	1.5	<1	.02	4
B 171182	.8	55	29	70	.8	38	16	745	4.43	75	3	<2	4	27	.6	1.0	1.1	29	.35	.123	24	25	.33	166	.006	<1	1.52	.004	.10	2	<1	4.1	<1	.02	6
B 171183	1.0	86	40	77	.8	56	28	2695	5.01	76	5	<2	5	26	.6	.9	1.3	27	.35	.136	23	28	.35	146	.007	<1	1.67	.006	.11	2	<1	5.6	1	.03	6
B 171184	.6	30	20	42	.2	21	8	352	2.79	31	2	<2	1	20	.3	.5	<.5	23	.27	.055	24	15	.22	90	.009	<1	.80	.003	.05	1	<1	1.3	<1	.01	4
STANDARD C3	27.8	71	36	174	5.8	36	12	795	3.34	57	25	<2	22	29	24.9	17.4	22.7	82	.58	.096	20	175	.61	158	.084	20	1.88	.041	.16	15	1	4.6	<1	.03	6
STANDARD G-2	1.7	3	4	48	<.1	8	4	549	2.05	<1	3	<2	4	75	<.2	<.5	<.5	43	.66	.106	9	81	.62	245	.128	<1	.99	.099	.51	3	<1	2.6	1	<.01	5

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
- SAMPLE TYPE: SOIL PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: NOV 23 2000 **DATE REPORT MAILED:** Nov 28/00 **SIGNED BY** .....D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 171185	1.0	38	18	60	.5	35	17	1344	3.83	51	2	<2	5	14	.6	.8	1.1	19	.18	.069	24	18	.30	71	.005	1	1.00	.004	.05	2	<1	3.0	<1	.02	3
B 171186	.6	24	15	66	.1	22	13	703	4.19	33	1	<2	3	6	.5	1.0	<.5	34	.06	.072	25	20	.16	90	.015	1	.89	.004	.05	2	<1	1.5	<1	.01	4
B 171187	.5	36	14	76	.3	30	12	445	4.21	38	1	<2	6	7	.6	1.6	<.5	27	.04	.060	25	21	.18	69	.009	1	1.19	.004	.05	2	<1	2.6	<1	.01	4
B 171188	1.0	48	29	69	.5	43	20	870	4.64	59	3	<2	3	19	.5	.5	1.0	28	.23	.087	24	24	.24	68	.009	1	1.21	.004	.07	2	<1	2.9	<1	.02	4
B 171189	.6	20	13	47	.2	22	10	342	2.48	26	1	<2	6	7	.2	<.5	<.5	18	.09	.039	33	17	.28	58	.012	1	.72	.003	.05	1	<1	1.8	1	<.01	2
B 171190	.7	46	28	63	.8	32	13	689	3.80	34	2	<2	2	17	.6	.9	<.5	30	.21	.089	23	27	.31	166	.009	1	1.29	.005	.10	2	<1	2.4	<1	.03	4
B 171191	.9	39	30	54	.6	30	13	767	3.21	61	1	<2	3	13	.6	.9	.9	19	.18	.064	22	15	.23	81	.007	<1	.73	.002	.05	2	<1	2.1	<1	.02	2
B 171192	.7	25	25	52	.7	23	11	348	3.44	32	1	<2	5	14	.4	<.5	.8	28	.15	.061	25	22	.28	189	.009	2	1.04	.004	.09	2	<1	2.5	<1	.01	3
B 171193	1.0	37	31	67	1.3	34	20	1332	4.06	42	2	<2	3	15	.6	.7	.7	27	.19	.090	24	26	.31	183	.008	1	1.24	.005	.10	2	<1	2.7	<1	.03	4
B 171194	.6	31	28	57	1.4	27	10	486	3.30	29	2	<2	3	14	.6	.7	.6	27	.17	.088	26	28	.33	182	.008	<1	1.25	.005	.10	2	<1	2.8	<1	.02	4
B 171195	.7	35	24	62	.3	33	13	691	3.56	38	1	<2	5	12	.5	<.5	.6	24	.17	.056	31	24	.33	109	.012	<1	.94	.003	.06	2	<1	2.8	<1	.01	3
B 171196	.6	32	24	57	.6	29	12	537	3.43	35	2	<2	3	14	.5	.8	.7	27	.18	.071	24	24	.30	156	.007	<1	1.15	.005	.09	2	<1	2.4	<1	.02	3
B 171197	.6	40	26	66	.5	33	14	581	3.97	37	2	<2	8	12	.6	<.5	<.5	32	.14	.052	29	29	.35	191	.009	<1	1.38	.004	.09	2	<1	3.8	<1	.01	3
B 171198	.9	30	24	62	.4	31	15	814	3.58	42	2	<2	4	19	.4	.9	.7	24	.28	.056	25	23	.37	142	.007	<1	1.05	.005	.07	2	<1	2.3	<1	.02	3
B 171199	.3	28	21	60	.2	30	14	439	3.65	34	2	<2	5	15	.4	<.5	<.5	28	.23	.048	26	27	.43	104	.007	<1	1.22	.004	.06	2	<1	2.2	<1	.01	3
B 171200	.7	34	28	51	.3	30	13	612	3.44	43	2	<2	4	8	.5	.6	1.1	18	.07	.065	23	18	.27	89	.005	1	1.01	.003	.05	2	<1	2.5	<1	.02	2
RE B 171200	.7	33	29	51	.3	30	13	612	3.47	43	2	<2	4	8	.5	.6	1.0	18	.07	.064	24	18	.27	90	.005	<1	1.01	.002	.05	2	<1	2.5	<1	.02	2
B 171201	.8	33	26	54	.4	32	12	531	3.60	46	2	<2	4	18	.4	<.5	1.0	20	.21	.062	24	21	.32	153	.004	<1	1.02	.005	.07	2	<1	2.2	<1	.02	2
B 171202	.5	27	21	63	.1	29	11	363	4.27	35	1	<2	7	8	.5	.6	<.5	29	.09	.048	32	31	.43	84	.012	<1	1.20	.003	.05	2	<1	2.0	<1	.01	3
B 171203	.5	37	28	60	.3	36	16	776	3.75	39	3	<2	6	17	.5	<.5	.6	27	.23	.074	28	25	.40	57	.010	<1	1.16	.003	.06	2	<1	3.2	<1	.01	3
B 171204	1.1	54	38	63	.4	44	18	1030	4.10	50	5	<2	5	24	.6	<.5	1.6	21	.34	.091	23	21	.35	66	.006	<1	1.17	.004	.06	2	<1	3.5	<1	.02	3
B 171205	1.3	56	31	75	.6	49	21	1620	4.63	60	6	<2	3	27	.6	.6	1.1	22	.34	.102	18	20	.27	77	.007	<1	1.15	.004	.07	2	<1	2.9	<1	.03	3
B 171206	1.7	63	26	65	1.3	54	22	2003	4.71	61	8	<2	2	42	.8	<.5	<.5	19	.61	.180	14	18	.23	78	.007	1	1.18	.006	.07	2	<1	3.2	<1	.06	3
B 171207	.9	31	18	54	.2	31	13	569	3.58	41	2	<2	3	18	.4	.8	<.5	21	.24	.090	20	17	.25	57	.009	<1	.81	.003	.05	2	<1	1.6	<1	.02	2
B 171208	1.4	32	17	62	.2	34	11	301	4.12	72	2	<2	2	15	.6	2.7	<.5	25	.14	.077	19	15	.14	49	.007	<1	.62	.002	.04	2	<1	1.2	<1	.01	2
B 171209	.6	32	27	62	.4	30	18	797	4.39	67	3	<2	2	24	.7	<.5	<.5	33	.35	.105	20	22	.27	82	.010	<1	1.13	.004	.05	2	<1	2.1	<1	.02	3
B 171210	1.7	36	16	65	.1	40	11	356	3.80	35	1	<2	3	5	.6	<.5	<.5	23	.05	.072	29	11	.06	48	.007	<1	.61	.002	.03	1	<1	1.1	1	.01	2
B 171211	.7	31	30	57	.4	27	11	449	4.10	39	2	<2	3	19	.5	.6	1.9	32	.27	.058	25	23	.26	71	.009	<1	1.18	.003	.06	2	<1	2.1	<1	.01	3
B 171212	.6	42	29	77	1.0	35	16	787	4.47	39	2	<2	3	14	.6	.5	.5	34	.14	.099	25	33	.37	200	.008	<1	1.68	.005	.13	2	<1	3.3	<1	.03	4
B 171213	.4	32	25	68	.4	31	16	1044	4.09	37	2	<2	4	13	.5	.5	<.5	30	.18	.066	23	29	.37	170	.008	<1	1.30	.004	.10	2	<1	2.3	<1	.02	3
B 171214	.5	19	18	55	.3	23	10	372	3.10	35	1	<2	3	9	.4	<.5	1.4	24	.11	.042	24	23	.33	103	.007	<1	1.01	.003	.07	1	<1	1.6	<1	.01	2
B 171215	.5	31	30	81	.3	35	16	957	4.52	39	1	<2	4	12	.5	<.5	<.5	37	.12	.074	21	34	.36	192	.008	1	1.56	.005	.13	2	<1	2.5	1	.02	4
B 171216	.4	24	19	62	<.1	29	12	356	3.20	31	1	<2	6	6	.4	.7	<.5	24	.09	.035	27	23	.35	90	.009	<1	.98	.002	.06	1	<1	1.8	<1	<.01	2
B 171217	.4	32	33	70	<.1	34	13	638	4.71	46	1	<2	5	11	.5	<.5	<.5	23	.17	.050	22	28	.34	105	.007	<1	1.23	.003	.07	2	<1	1.8	<1	.01	2
B 171218	.7	38	32	65	.3	36	16	605	4.17	52	3	<2	9	17	.5	.8	.8	24	.21	.065	29	23	.36	126	.006	<1	1.26	.004	.08	2	<1	3.8	<1	.01	2
STANDARD C3	28.9	70	36	170	6.3	36	11	836	3.48	58	27	<2	23	29	24.9	17.8	24.0	86	.61	.089	21	181	.64	167	.088	23	1.89	.041	.16	16	1	4.9	<1	.03	6
STANDARD G-2	1.5	3	3	44	<.1	7	4	545	2.02	<1	4	<2	5	72	<.2	<.5	<.5	42	.66	.097	9	80	.62	242	.129	<1	.93	.092	.49	2	<1	2.6	<1	<.01	4

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 171219	.7	36	28	67	.5	38	17	921	4.10	42	3	<2	4	21	.4	.7	1.8	27	.31	.082	27	27	.40	117	.007	2	1.40	.004	.10	2	<1	2.9	<1	.02	2
B 171220	.7	30	24	67	.2	32	14	477	3.73	36	1	<2	5	14	.3	.5	1.2	28	.16	.055	31	25	.35	90	.007	2	1.21	.003	.08	2	<1	2.2	<1	.01	2
B 171221	.6	25	19	52	.2	26	13	348	3.54	30	1	<2	6	9	.3	<.5	1.0	30	.11	.043	33	27	.37	77	.008	<1	1.18	.002	.06	2	<1	2.1	<1	.01	2
B 171222	.6	25	20	50	.2	31	12	363	3.54	34	1	<2	6	13	.3	<.5	.8	27	.19	.039	34	26	.43	57	.008	<1	1.15	.001	.05	2	<1	2.1	<1	<.01	1
B 171223	1.0	66	32	68	.4	54	24	1626	4.47	48	5	<2	6	23	.5	<.5	1.7	26	.31	.082	26	28	.45	93	.006	1	1.54	.004	.10	2	<1	4.1	1	.02	2
B 171224	.9	24	19	61	.1	28	10	388	4.22	33	<1	<2	5	8	.3	.6	1.2	26	.09	.062	32	25	.35	65	.007	<1	1.10	<.001	.05	2	<1	1.5	<1	<.01	2
B 171225	.8	25	24	67	.1	35	13	380	4.25	34	1	<2	6	6	.4	<.5	.8	29	.10	.056	31	32	.47	71	.012	1	1.32	.001	.05	2	<1	1.9	1	.01	2
B 171226	.7	17	19	60	.1	21	7	225	4.16	33	<1	<2	4	6	.4	<.5	1.0	33	.06	.053	26	26	.29	69	.010	1	1.15	.001	.04	2	<1	1.4	<1	.01	2
B 171227	.9	34	14	59	.3	42	15	359	3.33	34	2	<2	2	18	.3	.5	<.5	20	.25	.072	27	10	.11	60	.006	2	.53	<.001	.04	1	<1	1.3	<1	.02	1
B 171228	1.3	33	27	42	.5	33	12	808	3.11	84	4	<2	3	45	.6	1.0	2.2	24	.27	.087	26	17	.19	53	.004	2	.77	<.001	.05	1	<1	3.1	<1	.03	<1
B 171229	.9	52	27	61	.8	58	28	1154	4.46	55	5	<2	4	26	.6	.6	1.4	20	.39	.109	27	20	.27	64	.008	<1	1.05	.002	.07	1	<1	3.5	<1	.03	1
B 171230	2.0	97	106	84	1.0	77	29	1533	5.76	105	6	<2	4	25	.8	1.0	3.4	18	.34	.142	28	20	.23	68	.007	<1	1.08	.002	.08	2	<1	4.8	1	.04	2
B 171231	.9	30	29	67	.2	28	10	331	4.35	33	2	<2	4	18	.5	<.5	.7	41	.21	.050	28	28	.34	80	.018	<1	1.18	.001	.05	2	<1	2.0	<1	.01	3
B 171232	.8	21	21	60	.3	24	11	342	3.46	27	1	<2	5	8	.3	.6	1.2	32	.08	.042	26	26	.31	136	.009	<1	1.36	.002	.11	2	<1	2.3	<1	.01	3
B 171233	.5	5	6	10	.1	4	1	45	.91	12	<1	<2	3	4	<.2	<.5	.8	16	.04	.018	34	7	.06	51	.006	1	.48	<.001	.03	1	<1	.5	<1	<.01	4
B 171234	.5	28	24	79	.1	33	10	247	4.49	33	1	<2	9	9	.5	.5	.5	33	.10	.032	30	31	.34	149	.010	1	1.48	.002	.11	2	<1	2.5	<1	<.01	3
B 171235	.7	35	29	60	.8	34	15	626	3.88	44	2	<2	4	8	.5	.7	2.0	24	.08	.071	28	23	.32	101	.006	1	1.21	.001	.08	2	<1	2.7	<1	.02	1
B 171236	.5	25	24	68	.3	29	11	337	3.81	28	1	<2	5	11	.5	<.5	<.5	32	.13	.037	28	28	.35	109	.011	<1	1.25	.002	.08	1	<1	2.0	<1	.01	3
B 171237	.8	21	21	65	.2	27	10	352	3.17	27	1	<2	5	14	.3	.6	.5	31	.19	.043	32	24	.35	109	.012	<1	1.02	.001	.08	1	<1	2.0	<1	<.01	2
B 171238	.6	29	27	63	.3	32	15	587	3.76	31	2	<2	5	16	.5	<.5	.8	30	.18	.049	31	27	.40	102	.010	<1	1.28	.002	.09	2	<1	2.9	<1	.01	2
B 171239	.5	37	23	64	.4	39	14	612	3.75	28	3	<2	4	24	.6	<.5	1.1	30	.35	.062	29	30	.45	109	.009	1	1.36	.002	.10	1	<1	2.9	<1	.02	3
B 171240	.5	44	23	55	.9	44	14	809	3.29	33	5	<2	3	45	.5	<.5	1.4	21	.71	.101	21	22	.37	104	.007	3	1.25	.004	.09	2	<1	3.0	<1	.05	2
RE B 171240	.7	43	22	53	.9	43	13	794	3.22	32	5	<2	3	44	.4	<.5	1.6	21	.70	.099	21	22	.37	102	.007	2	1.23	.003	.09	2	<1	2.9	<1	.05	2
B 171241	.7	41	29	66	.8	46	18	1060	4.23	43	4	<2	5	23	.5	<.5	1.7	26	.31	.084	27	28	.42	111	.008	2	1.50	.003	.10	2	<1	3.6	<1	.03	2
B 171242	.7	33	25	63	.4	38	17	698	4.11	31	2	<2	5	21	.4	<.5	1.3	34	.29	.054	32	33	.48	94	.011	<1	1.40	.002	.08	1	<1	2.8	<1	.01	3
B 171243	.9	29	22	54	.4	34	15	506	3.68	48	2	<2	5	10	.5	.5	1.6	23	.13	.040	35	20	.34	48	.009	<1	.95	<.001	.04	2	<1	1.9	<1	<.01	2
B 171244	.8	26	21	57	.2	32	14	503	3.76	37	2	<2	5	16	.5	<.5	1.4	28	.24	.053	27	27	.40	76	.009	1	1.16	.002	.06	2	<1	2.2	<1	.01	2
B 171245	.7	18	15	42	.1	17	8	430	3.78	34	<1	<2	7	4	.4	1.2	.7	33	.04	.065	32	16	.14	46	.022	<1	.73	<.001	.03	2	<1	1.3	1	<.01	3
B 171246	.7	28	23	69	.6	35	19	4356	3.71	28	5	<2	1	25	.4	<.5	.7	27	.34	.087	21	18	.17	166	.010	2	.94	.002	.06	1	<1	1.5	2	.03	3
B 171247	1.1	68	22	86	.7	71	22	1826	4.97	40	6	<2	3	35	.9	1.3	1.1	28	.37	.101	25	22	.21	92	.009	1	1.17	.002	.06	2	<1	3.2	1	.03	3
B 171248	.9	76	36	59	1.2	56	22	1791	4.18	36	8	<2	2	29	.9	<.5	1.4	22	.39	.112	25	22	.28	75	.011	3	1.25	.002	.07	1	<1	3.7	<1	.04	2
B 171249	1.0	26	23	51	.3	30	18	837	3.62	43	2	<2	5	13	.5	.7	1.1	18	.16	.052	28	18	.29	51	.008	1	.87	<.001	.05	3	<1	2.0	<1	.01	1
B 171250	1.3	30	53	54	.5	29	11	375	4.09	45	3	<2	3	20	.6	<.5	2.1	27	.29	.061	25	19	.23	55	.009	1	1.04	.001	.06	2	<1	1.8	<1	.02	3
B 171251	.8	32	68	65	.4	29	15	831	4.54	39	3	<2	4	20	.5	1.0	1.5	32	.27	.055	26	27	.27	83	.012	1	1.22	.002	.07	2	<1	2.1	1	.01	3
B 171252	.7	27	24	59	.2	32	12	455	3.42	32	2	<2	6	12	.5	<.5	.7	23	.15	.053	32	24	.36	101	.008	2	1.14	.002	.08	2	<1	2.7	<1	.01	2
STANDARD C3	27.3	69	38	180	5.9	38	12	821	3.48	60	25	<2	22	30	25.0	14.0	24.3	86	.62	.100	21	186	.64	164	.093	24	1.89	.038	.17	15	1	4.7	<1	.03	5
STANDARD G-2	1.8	3	3	46	<.1	8	4	571	2.13	<1	4	<2	4	75	<.2	<.5	<.5	43	.70	.109	9	86	.64	242	.136	5	.93	.075	.50	3	<1	2.7	<1	<.01	4

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 171253	.6	40	32	78	.4	36	15	595	4.17	31	2	<2	5	19	.7	<.5	1.1	35	.24	.065	29	37	.39	170	.009	1	1.61	.006	.17	2	<1	3.2	<1	.02	3
B 171254	.9	38	26	78	.5	38	14	694	4.44	37	3	<2	6	19	.6	<.5	1.2	34	.23	.083	29	35	.42	167	.008	3	1.72	.006	.17	3	<1	3.9	<1	.02	4
B 171255	.7	45	32	88	.4	45	20	963	4.77	38	3	<2	7	22	.6	.5	1.1	38	.25	.063	30	40	.47	160	.009	2	1.82	.005	.15	2	1	4.1	<1	.02	4
B 171256	.5	31	27	73	.4	38	17	524	4.24	40	2	<2	7	22	.5	<.5	1.5	26	.29	.062	30	30	.46	119	.008	3	1.46	.004	.10	2	<1	2.9	<1	.02	3
B 171257	.5	34	23	70	.6	37	13	558	4.13	39	3	<2	6	18	.5	<.5	1.4	29	.25	.079	30	29	.43	103	.008	2	1.42	.003	.10	2	1	3.3	<1	.02	3
B 171258	.4	35	23	61	.2	37	16	714	3.81	36	2	<2	9	12	.4	.6	1.3	23	.18	.054	38	26	.43	64	.011	2	1.07	.002	.07	2	<1	3.0	1	<.01	2
B 171259	.7	40	35	83	.3	42	18	859	5.07	40	3	<2	6	22	.6	<.5	1.3	39	.28	.057	26	40	.42	121	.012	3	1.58	.004	.11	2	<1	3.2	<1	.02	4
B 171260	.6	29	20	65	.2	37	14	545	3.89	32	2	<2	5	16	.5	<.5	1.0	29	.19	.055	29	34	.46	87	.011	1	1.32	.003	.08	4	<1	2.9	<1	.01	3
B 171261	.8	61	29	84	1.0	48	18	754	5.09	49	4	<2	6	22	.5	.6	2.3	33	.24	.097	29	34	.37	134	.009	2	1.77	.004	.12	3	<1	5.1	<1	.02	5
B 171262	1.2	79	33	78	.6	58	20	1023	5.31	55	6	<2	7	27	.2	1.1	2.6	31	.35	.112	27	36	.40	126	.007	2	1.94	.005	.15	2	1	5.8	1	.03	5
B 171263	.6	26	23	62	.1	28	10	268	4.59	49	<1	<2	11	4	.4	<.5	1.7	25	.03	.033	36	29	.38	64	.010	<1	1.27	.001	.05	4	<1	1.9	<1	.01	3
B 171264	.8	30	15	70	.1	24	12	600	4.52	29	1	<2	7	5	.4	.6	1.3	28	.04	.060	29	22	.22	53	.009	1	1.10	.001	.05	16	<1	1.7	<1	.01	3
B 171265	.4	25	25	83	.2	31	11	302	5.28	23	1	<2	6	9	.3	.7	.7	30	.07	.051	28	32	.33	92	.008	<1	1.45	.002	.05	2	1	2.2	2	.01	5
B 171266	1.5	94	104	82	1.6	96	38	1460	5.88	93	6	<2	7	24	.6	2.1	13.8	12	.26	.122	37	16	.15	57	.005	<1	.91	.002	.07	4	<1	4.3	1	.02	3
B 171267	.7	22	24	69	.2	23	13	674	3.93	35	2	<2	5	13	.3	<.5	1.3	30	.14	.042	30	24	.25	59	.014	1	1.18	.002	.07	2	<1	1.9	<1	.01	3
B 171268	1.0	44	20	57	.8	38	19	853	4.23	64	3	<2	5	16	.4	.6	1.3	18	.20	.059	31	16	.15	59	.007	2	.83	.001	.06	2	<1	2.6	1	.02	2
B 171269	.9	27	27	54	.3	24	10	627	3.41	30	2	<2	4	13	.2	.6	1.2	24	.12	.051	29	15	.11	74	.011	<1	.76	<.001	.05	3	<1	1.8	<1	.01	2
B 171270	.6	29	28	63	.3	37	16	568	4.84	34	1	<2	8	5	.5	<.5	1.1	29	.04	.043	29	31	.34	80	.008	1	1.57	.002	.07	3	1	2.1	1	.01	4
RE B 171270	.6	29	29	64	.3	38	17	568	4.85	34	1	<2	8	5	.5	<.5	1.5	29	.04	.043	29	32	.34	81	.009	<1	1.58	.001	.07	2	1	2.1	1	.01	4
B 171271	.8	27	26	57	.5	29	12	455	3.51	31	2	<2	7	17	.2	.6	1.4	23	.21	.058	30	23	.31	99	.007	<1	1.19	.002	.09	2	<1	3.1	<1	.01	3
B 171272	<.2	29	24	63	.2	32	13	592	3.73	34	2	<2	6	15	.3	.5	1.1	25	.19	.062	29	26	.35	102	.007	<1	1.29	.002	.09	2	<1	2.9	<1	.01	3
B 171273	.3	27	19	60	<.1	34	12	399	3.38	26	1	<2	9	10	.2	.5	.9	21	.13	.046	39	26	.44	74	.009	<1	1.14	.002	.06	2	<1	2.3	<1	<.01	3
B 171274	.2	27	24	74	.1	35	14	393	3.71	30	1	<2	7	8	.3	<.5	.9	27	.11	.032	35	27	.40	128	.009	1	1.21	.002	.08	2	1	2.2	1	<.01	3
B 171275	.5	30	24	70	.4	35	14	773	3.95	34	2	<2	6	18	.4	<.5	.9	28	.25	.061	28	27	.38	112	.007	<1	1.42	.003	.11	2	<1	3.1	<1	.01	4
B 171276	.4	25	19	62	.3	28	11	426	3.33	27	1	<2	6	11	.3	.6	.9	28	.14	.045	32	26	.37	120	.006	<1	1.31	.002	.09	2	<1	2.6	<1	<.01	4
B 171277	.4	23	18	56	.1	24	10	342	3.20	27	1	<2	7	10	.3	.6	1.1	24	.15	.036	34	23	.34	90	.005	<1	1.12	.002	.06	1	<1	2.2	<1	<.01	3
B 171278	.2	26	23	54	.2	26	9	138	2.44	20	1	<2	5	12	.2	.5	.8	24	.19	.045	30	24	.37	84	.008	<1	1.13	.002	.07	1	<1	2.6	<1	.01	3
B 171279	.5	31	23	69	.3	33	17	804	3.93	30	2	<2	5	11	.3	.7	1.3	28	.15	.055	30	30	.43	102	.009	<1	1.32	.001	.08	2	<1	3.1	<1	.01	4
B 171280	.2	36	21	70	.2	41	21	808	4.07	35	2	<2	6	11	.3	<.5	1.6	29	.17	.050	34	39	.49	78	.017	<1	1.24	.002	.06	2	<1	3.5	<1	<.01	4
B 171281	<.2	29	15	60	.1	35	15	321	3.73	24	1	<2	10	6	<.2	.6	.7	24	.07	.025	38	31	.56	59	.009	1	1.27	.001	.05	2	<1	2.5	<1	<.01	4
B 171282	.4	31	32	59	.1	23	12	554	3.80	37	1	<2	7	6	.3	.5	1.6	26	.05	.030	30	21	.27	58	.008	<1	1.10	.001	.06	2	<1	1.7	1	<.01	3
B 171283	.5	32	25	63	.3	35	14	706	3.59	37	2	<2	7	12	.2	.6	1.6	22	.14	.043	33	20	.34	44	.011	1	1.06	.001	.04	2	<1	2.5	<1	.01	3
B 171284	.5	27	32	57	.4	21	11	422	3.55	30	1	<2	9	9	.3	.9	1.8	28	.10	.030	33	25	.28	70	.009	1	1.28	.002	.06	3	<1	2.0	<1	.01	4
B 171285	.2	26	22	49	.2	30	11	562	3.23	26	2	<2	6	16	<.2	<.5	1.3	26	.22	.042	32	26	.33	75	.007	<1	1.27	.001	.07	2	1	2.4	<1	<.01	4
B 171286	<.2	21	19	55	.2	28	13	410	3.59	26	1	<2	6	13	.2	<.5	.9	25	.17	.049	33	27	.41	66	.009	<1	1.19	.001	.06	2	<1	1.9	<1	<.01	4
STANDARD C3	26.5	70	38	175	5.8	36	11	813	3.42	61	25	2	23	31	25.1	16.9	24.3	84	.62	.096	20	180	.63	159	.091	22	1.89	.040	.17	16	1	4.7	<1	.03	6
STANDARD G-2	1.6	3	3	44	<.1	7	4	538	2.01	<1	4	<2	4	73	<.2	<.5	<.5	39	.67	.100	9	78	.60	221	.128	2	.89	.076	.46	3	<1	2.6	<1	<.01	4

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 171287	.6	42	25	61	.2	39	14	566	3.82	42	2	<2	7	10	.4	<.5	2.8	23	.13	.057	36	25	.39	59	.007	2	1.19	.002	.06	2	<1	3.4	1	.01	3
B 171288	1.0	26	14	52	.4	23	7	360	2.92	26	1	<2	5	14	.2	<.5	1.6	21	.18	.056	37	17	.17	83	.006	1	1.05	.002	.07	1	<1	2.2	<1	.01	3
B 171289	.5	15	12	33	.2	16	9	235	2.15	12	1	<2	6	10	<.2	<.5	.6	14	.15	.065	44	10	.16	38	.010	4	.55	<.001	.04	1	<1	1.1	<1	<.01	1
B 171290	.8	38	29	65	.3	37	15	558	3.78	33	2	<2	8	22	.3	.6	1.2	24	.32	.061	38	23	.35	96	.007	2	1.12	.003	.10	2	<1	3.0	<1	.02	3
B 171291	.8	45	38	75	.3	44	20	792	3.90	39	2	<2	15	27	.4	<.5	1.4	22	.44	.073	46	20	.32	90	.008	2	.93	.002	.09	2	<1	3.4	<1	.01	2
B 171292	.6	33	28	61	.2	34	16	480	3.61	28	1	<2	8	11	.3	.5	1.0	30	.15	.044	39	27	.37	97	.009	1	1.22	.001	.08	2	<1	3.2	1	<.01	3
B 171293	.5	33	31	67	.3	34	13	215	3.51	30	2	<2	7	13	.4	.5	1.5	27	.18	.057	36	28	.39	102	.007	<1	1.42	.002	.10	2	<1	3.5	<1	.01	3
B 171294	.7	33	28	67	.3	34	13	586	3.59	32	2	<2	7	14	.3	<.5	1.3	25	.19	.057	37	27	.37	89	.006	<1	1.21	.001	.08	2	<1	3.0	2	<.01	3
B 171295	.4	53	32	69	.4	41	17	707	4.51	34	3	<2	6	19	.6	.9	1.1	31	.25	.070	33	32	.38	101	.008	<1	1.50	.002	.10	2	<1	3.8	1	.02	3
B 171296	.4	43	29	71	.4	40	15	711	4.38	35	2	<2	6	22	.4	<.5	1.4	28	.29	.085	31	30	.40	102	.007	1	1.44	.002	.11	2	<1	3.7	<1	.02	3
B 171297	.2	34	31	66	.7	36	12	256	3.26	25	2	<2	6	13	.3	.6	1.8	26	.16	.063	34	27	.40	83	.007	2	1.36	.002	.09	2	<1	3.0	<1	.01	3
B 171298	.3	37	31	66	.9	36	12	348	3.57	30	3	<2	5	19	.4	<.5	1.5	27	.29	.083	33	27	.37	84	.007	<1	1.39	.002	.09	2	<1	3.6	<1	.02	3
B 171299	.3	25	23	62	.2	32	13	416	3.46	32	1	<2	8	12	.2	<.5	.8	27	.15	.040	38	25	.40	78	.009	<1	1.17	.001	.08	2	<1	2.4	1	<.01	2
B 171300	<.2	28	27	72	.1	30	11	339	3.61	30	<1	<2	10	7	.3	<.5	.7	27	.06	.029	38	27	.37	119	.007	<1	1.30	.001	.09	2	<1	2.4	2	<.01	2
RE B 171300	.2	28	27	74	.1	31	11	348	3.70	32	<1	<2	10	7	.3	.8	.9	28	.06	.030	39	27	.38	122	.007	<1	1.33	.001	.10	2	<1	2.4	<1	<.01	2
B 171301	.2	30	28	70	.1	35	17	467	4.17	38	1	<2	9	6	.4	.5	1.0	24	.06	.035	38	28	.41	57	.008	1	1.28	<.001	.06	2	<1	2.2	1	<.01	2
B 171302	.4	28	29	53	.3	29	12	369	3.06	34	1	<2	7	9	.2	<.5	2.3	20	.11	.037	40	16	.26	51	.004	<1	.93	<.001	.05	2	<1	2.4	2	<.01	1
B 171303	.4	31	29	81	.1	31	11	279	5.25	37	1	<2	7	11	.3	.5	1.7	32	.15	.043	33	29	.45	61	.008	<1	1.44	<.001	.04	3	<1	2.2	<1	.01	3
B 171304	.7	31	24	72	.1	34	12	350	5.41	46	1	<2	8	7	.5	1.0	1.0	28	.04	.048	34	22	.17	67	.011	<1	.89	<.001	.05	3	<1	1.4	2	.01	3
B 171305	.6	27	22	63	.1	30	14	598	4.05	31	2	<2	6	14	.3	<.5	1.0	27	.15	.057	31	24	.30	65	.009	<1	1.18	<.001	.07	3	<1	2.4	<1	.01	2
B 171306	.5	23	17	54	.1	23	7	245	4.13	25	1	<2	6	10	.3	.5	.8	31	.12	.034	35	26	.28	49	.008	<1	1.10	<.001	.04	2	<1	1.6	1	<.01	2
B 171307	1.8	55	97	72	1.7	52	19	1364	5.09	58	5	<2	5	22	.5	1.1	5.2	22	.30	.119	27	25	.26	75	.007	<1	1.18	.001	.08	5	<1	4.2	<1	.03	2
B 171308	1.7	46	24	46	.6	43	18	1103	4.82	150	3	<2	12	13	.5	.5	5.9	10	.14	.068	60	11	.12	39	.003	<1	.59	<.001	.04	2	<1	3.0	3	.01	<1
B 171519	.5	28	22	63	.6	25	9	363	3.88	42	1	<2	4	10	.3	.7	1.7	30	.09	.060	33	27	.30	115	.010	1	1.37	.001	.10	4	<1	2.0	1	.01	2
B 171520	.4	30	21	71	.4	28	11	426	4.57	54	1	<2	8	9	.5	<.5	1.6	31	.08	.053	35	26	.28	97	.012	<1	1.28	.001	.09	3	<1	2.4	1	.01	2
B 171521	.3	35	26	66	.7	24	9	440	3.70	27	1	<2	3	12	.5	<.5	1.4	39	.09	.072	31	31	.27	168	.010	1	1.59	.004	.15	2	<1	2.5	1	.01	3
B 171522	.4	24	21	64	.4	28	9	278	3.75	33	1	<2	6	8	.4	.5	.7	34	.09	.047	34	29	.35	105	.011	<1	1.37	<.001	.09	2	<1	2.4	1	.01	2
B 171523	.2	28	20	65	.3	34	11	351	3.97	37	1	<2	4	11	.3	.5	1.1	36	.13	.063	33	35	.41	107	.016	<1	1.34	.001	.10	3	<1	2.2	1	.01	2
B 171524	.3	19	19	48	.3	18	8	797	2.65	31	2	<2	2	16	.2	<.5	1.7	28	.18	.061	30	17	.23	117	.006	<1	.98	<.001	.06	2	<1	1.3	<1	.01	2
B 171525	.2	21	17	57	.4	24	11	422	3.49	37	1	<2	4	11	.3	<.5	1.2	28	.13	.054	30	24	.33	62	.007	<1	1.14	<.001	.06	2	<1	1.7	1	<.01	1
B 171526	.2	28	20	67	.1	28	10	294	4.37	48	1	<2	7	6	.5	.6	1.4	24	.06	.053	36	25	.35	79	.005	<1	1.31	<.001	.06	3	<1	1.9	2	<.01	1
B 171527	.8	30	27	52	.5	27	12	603	3.31	55	1	<2	6	8	.3	<.5	1.7	17	.05	.044	35	14	.20	56	.003	<1	.75	<.001	.05	3	<1	1.9	1	.01	<1
B 171528	.8	45	44	64	.1	42	16	526	4.16	87	1	<2	14	16	.4	.6	2.7	14	.04	.039	37	13	.24	53	.005	<1	.73	<.001	.06	5	<1	2.9	1	<.01	<1
B 171529	.6	29	22	55	.3	30	13	580	3.66	78	2	<2	6	12	.3	.9	1.9	18	.12	.056	34	16	.27	45	.004	<1	.89	<.001	.05	2	<1	2.0	2	.01	<1
B 171530	.6	30	20	62	.4	36	19	888	4.88	79	3	<2	4	20	.4	<.5	1.2	28	.22	.092	28	25	.29	87	.006	<1	1.38	.002	.09	2	<1	2.4	1	.02	1
STANDARD C3	26.4	68	35	174	5.7	37	11	791	3.33	57	24	2	22	30	25.2	16.6	23.7	85	.60	.094	21	180	.62	159	.089	23	1.84	.039	.17	16	1	4.6	1	.03	5
STANDARD G-2	1.5	3	3	46	<.1	7	4	567	2.10	<1	4	<2	6	77	<.2	<.5	<.5	43	.70	.106	9	84	.63	237	.137	5	.94	.083	.48	3	<1	2.8	<1	<.01	4

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 171531	.2	26	20	81	.1	33	14	533	4.78	39	1	<2	3	7	.4	.5	<.5	40	.10	.129	33	42	.40	88	.029	1	1.24	.004	.07	2	<1	2.1	1	.01	4
B 171532	1.3	62	26	101	.9	57	26	2339	6.05	105	4	<2	4	26	.8	<.5	1.8	30	.32	.158	28	22	.28	127	.006	2	1.39	.007	.13	2	<1	3.7	2	.03	4
B 171533	.3	34	24	73	.2	33	16	516	4.46	45	1	<2	6	11	.4	<.5	<.5	27	.12	.064	37	22	.38	86	.005	1	1.38	.003	.08	2	<1	2.3	1	.01	3
B 171534	.3	23	21	79	.2	24	9	331	4.59	33	1	<2	5	7	.5	<.5	<.5	32	.10	.062	30	25	.32	115	.008	<1	1.28	.002	.07	2	<1	1.7	<1	.01	4
B 171535	.3	21	16	64	.1	22	10	355	3.61	32	1	<2	4	8	.4	<.5	<.5	28	.09	.043	32	22	.29	66	.006	<1	1.14	.001	.05	5	<1	1.6	2	<.01	3
B 171536	.2	27	22	76	.2	31	16	508	3.94	34	1	<2	6	8	.3	<.5	<.5	24	.08	.043	34	22	.38	71	.006	<1	1.25	.001	.06	3	<1	1.9	<1	<.01	3
B 171537	.9	27	23	70	.3	28	14	450	4.11	37	1	<2	4	10	.4	.5	<.5	26	.14	.080	29	21	.33	67	.005	<1	1.19	.001	.07	2	<1	1.6	<1	.02	3
B 171538	1.1	24	17	66	.1	25	9	249	5.59	39	1	<2	5	7	.3	.5	1.0	25	.09	.056	26	24	.28	79	.006	<1	1.09	<.001	.03	2	<1	1.6	1	.02	3
B 171539	.4	21	17	56	.2	25	10	386	3.55	35	1	<2	6	7	.3	<.5	<.5	22	.07	.039	38	22	.39	68	.009	<1	1.09	.001	.05	2	<1	1.6	<1	<.01	2
B 171540	.4	24	40	58	.3	17	11	696	3.50	36	1	<2	6	9	.4	.5	1.0	27	.10	.038	33	20	.23	84	.010	<1	1.11	.002	.07	2	<1	1.8	2	.01	3
B 171541	.7	24	20	58	1.3	21	8	342	3.87	50	1	<2	2	14	.4	<.5	1.5	27	.10	.079	31	18	.21	83	.010	1	.99	.001	.07	2	<1	1.4	1	.02	2
B 171542	.6	32	25	74	.3	31	15	731	4.08	40	1	<2	5	9	.4	.9	.5	33	.08	.051	36	29	.39	109	.013	<1	1.36	.003	.11	2	<1	2.6	2	.01	3
B 171543	.5	35	30	78	.5	35	16	599	5.00	50	1	<2	5	9	.5	<.5	.6	36	.12	.093	31	32	.37	134	.016	1	1.54	.004	.13	4	<1	2.8	1	.01	4
B 171544	.3	35	27	84	.2	37	14	461	4.66	37	1	<2	6	9	.5	<.5	<.5	33	.10	.074	29	32	.38	152	.015	<1	1.52	.003	.13	3	<1	2.8	1	.01	3
B 171545	.4	23	22	65	.2	22	8	364	3.89	27	1	<2	3	6	.4	<.5	<.5	39	.06	.079	27	27	.26	120	.011	<1	1.40	.002	.11	2	<1	2.1	1	.02	3
RE B 171545	.4	22	23	64	.2	22	8	370	3.91	27	1	<2	3	5	.4	<.5	<.5	38	.06	.079	28	27	.26	119	.011	<1	1.39	.002	.10	2	<1	2.1	2	.02	3
B 171546	.4	33	26	63	.3	32	14	611	3.58	48	1	<2	6	8	.4	.5	1.1	22	.07	.054	33	18	.31	64	.008	<1	.95	<.001	.06	2	<1	2.1	1	.01	1
B 171547	.2	11	14	40	.4	14	4	174	3.34	17	1	<2	3	4	.4	<.5	<.5	38	.08	.087	23	22	.24	59	.011	<1	1.12	<.001	.04	2	<1	1.2	1	.01	3
B 171548	.7	30	20	58	.4	32	12	501	3.62	52	2	<2	6	14	.3	.8	1.2	18	.14	.063	33	16	.24	98	.003	<1	1.07	<.001	.06	2	<1	2.3	<1	.01	1
B 171549	.7	33	21	65	.2	28	12	381	4.55	52	2	<2	5	11	.4	.7	1.5	25	.15	.099	30	19	.26	112	.006	<1	1.01	<.001	.05	2	<1	1.7	1	.02	2
B 171550	.4	18	17	67	.1	23	13	870	4.40	80	1	<2	3	7	.5	.8	.9	37	.07	.107	30	14	.09	59	.012	<1	.74	.001	.05	2	<1	1.3	2	.01	3
STANDARD C3	27.6	64	37	180	5.9	37	12	850	3.47	59	25	2	21	31	24.8	16.5	24.6	86	.63	.099	21	179	.65	164	.093	25	1.84	.041	.17	14	1	4.8	<1	.03	5
STANDARD G-2	1.6	3	3	45	<.1	7	4	571	2.05	<1	5	<2	4	76	<.2	1.0	<.5	42	.69	.102	10	78	.62	230	.131	1	.93	.080	.48	2	<1	2.8	<1	<.01	4

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data 1/ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) 3-17-16
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004087 Page 1

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
351351	2.8	41	21	76	1.5	98	24	136	1.84	50	74	<2	1	63	1.1	<.5	.6	21	.81	.091	15	31	.22	364	.006	2	1.06	.008	.05	<1	<1	3.6	<1	.58	2
351352	3.1	28	8	466	.2	279	44	71	2.34	10	34	<2	4	10	2.9	.7	<.5	16	.13	.026	11	16	.22	116	.019	1	.52	.004	.05	1	<1	2.2	<1	.94	1
351353	3.1	42	20	148	.3	109	25	44	1.07	16	3	<2	5	16	1.8	1.2	<.5	15	.19	.052	14	17	.27	146	.013	1	.60	.005	.04	1	<1	2.6	<1	.35	1
351354	3.2	49	24	66	.5	41	8	44	1.07	7	4	<2	4	17	.4	1.4	<.5	17	.18	.061	16	18	.30	226	.013	1	.67	.003	.04	<1	<1	3.6	<1	.26	1
351355	.6	9	12	76	.1	26	4	61	1.29	2	1	<2	8	17	<.2	<.5	<.5	14	.18	.047	30	15	.34	143	.011	1	.74	.003	.03	1	<1	1.8	<1	.02	2
351356	1.3	46	28	94	.3	49	17	730	3.47	25	2	<2	8	25	.2	.6	<.5	25	.33	.065	25	24	.47	199	.026	1	.90	.009	.09	1	<1	3.6	<1	.02	2
351357	.5	26	17	66	.1	32	11	238	1.91	15	2	<2	6	32	.2	.9	<.5	14	.61	.062	21	12	.33	98	.014	<1	.54	.003	.04	1	<1	2.3	<1	.11	1
351358	.9	51	24	89	.2	46	16	640	3.44	27	2	<2	8	72	.2	.5	<.5	25	1.40	.063	24	23	.46	163	.022	4	1.01	.012	.14	1	<1	3.9	<1	.04	2
351359	.8	35	34	74	.2	37	15	699	3.33	30	2	<2	8	19	.2	1.1	.5	19	.25	.062	24	16	.25	66	.022	<1	.63	.003	.04	2	<1	2.9	<1	.02	1
351362	1.3	32	29	73	.1	41	14	601	3.38	26	3	<2	8	19	.2	.7	<.5	14	.37	.063	25	21	.27	76	.009	<1	.52	.003	.04	2	<1	2.8	<1	.05	1
351363	.4	41	31	74	.1	77	22	685	4.41	47	2	<2	8	22	<.2	.5	.5	17	.36	.078	29	18	.31	46	.012	<1	.57	.002	.04	2	<1	3.7	<1	.03	1
351364	1.3	48	37	100	.2	84	23	796	5.48	45	2	<2	7	30	<.2	.6	.7	34	.59	.083	23	66	.60	71	.009	<1	1.03	.004	.06	2	<1	4.8	<1	.04	2
351365	.8	55	22	63	.1	49	35	794	3.78	66	2	<2	11	21	<.2	1.0	.6	12	.31	.070	29	13	.23	61	.006	1	.55	.003	.07	1	<1	2.7	<1	.02	1
RE 351365	.6	57	22	62	.1	48	34	782	3.72	66	2	<2	11	21	.2	.7	<.5	12	.31	.067	28	13	.23	60	.005	2	.54	.004	.07	1	<1	2.7	<1	.03	1
351366	.7	42	34	81	.4	46	18	713	3.68	47	2	<2	10	104	<.2	<.5	.5	22	2.09	.060	24	27	.54	103	.013	2	1.09	.010	.15	1	<1	3.7	<1	.04	3
351367	.6	52	34	97	.1	44	21	820	4.04	28	1	<2	11	59	<.2	<.5	.5	30	1.38	.072	29	29	.66	92	.022	3	1.23	.008	.10	1	<1	4.1	<1	.02	3
351368	.6	29	27	84	.4	36	12	432	3.77	25	2	<2	5	17	.2	<.5	.5	30	.18	.066	31	32	.33	185	.010	<1	1.64	.007	.14	1	<1	4.2	1	.01	3
351369	.7	47	42	83	.1	48	22	898	4.38	55	2	<2	13	18	<.2	<.5	.8	22	.22	.051	36	22	.32	140	.012	<1	1.13	.011	.18	2	<1	4.3	1	<.01	2
351370	.7	37	33	68	.3	40	14	816	3.65	32	2	<2	8	12	.2	.5	.6	25	.17	.054	38	26	.32	157	.011	<1	1.22	.005	.11	2	<1	4.6	<1	<.01	2
351371	.4	46	38	90	<.1	51	20	793	4.10	45	1	<2	10	8	.2	<.5	<.5	32	.06	.036	36	35	.49	149	.022	<1	1.41	.008	.16	2	<1	5.0	<1	<.01	3
351372	.5	39	29	72	.1	36	16	624	3.88	46	1	<2	10	5	<.2	.7	<.5	22	.05	.031	35	19	.30	87	.009	<1	1.05	.005	.11	1	<1	2.8	<1	<.01	2
351373	1.2	61	30	154	.4	84	23	548	5.19	23	2	<2	7	12	.2	.9	.5	27	.13	.076	23	37	.35	189	.008	<1	1.90	.004	.12	2	1	3.6	<1	.02	2
351374	1.1	52	24	116	.2	66	23	498	3.97	20	1	<2	5	9	.2	.7	<.5	16	.10	.073	18	27	.27	84	.007	<1	1.48	<.001	.04	1	<1	2.4	<1	.01	1
351375	1.2	46	27	104	.2	56	17	410	5.42	22	1	<2	5	7	<.2	.5	<.5	21	.06	.088	20	31	.27	99	.008	<1	1.25	.001	.06	1	<1	2.2	<1	.02	1
351376	.8	44	41	93	.2	50	17	520	3.67	45	1	<2	10	5	<.2	<.5	.6	21	.04	.046	38	22	.32	91	.012	3	1.19	.004	.10	2	<1	3.2	1	<.01	2
351377	.4	38	35	83	<.1	39	17	586	3.84	42	1	<2	11	7	<.2	<.5	<.5	27	.05	.043	39	26	.42	84	.025	<1	1.31	.011	.13	2	<1	3.8	1	<.01	3
351378	.9	29	24	81	.2	35	13	224	4.17	28	1	<2	9	4	.2	.7	<.5	25	.03	.049	31	30	.34	77	.009	<1	1.58	.001	.06	2	<1	2.4	1	<.01	2
351379	.5	46	51	88	<.1	44	20	1012	4.32	39	1	<2	12	8	.2	<.5	<.5	27	.06	.055	38	26	.47	136	.023	<1	1.33	.007	.11	2	<1	4.9	1	<.01	3
351381	.6	29	24	91	.2	37	14	318	4.09	31	1	<2	7	7	<.2	<.5	<.5	28	.09	.063	35	29	.46	91	.013	<1	1.42	.003	.07	1	<1	2.6	<1	<.01	3
351382	.6	63	8	110	.1	46	25	654	4.41	38	1	<2	9	3	<.2	.6	<.5	4	.02	.046	44	7	.08	43	.003	<1	.40	.002	.05	1	<1	1.6	<1	<.01	<1
351383	<.2	20	4	33	<.1	42	19	594	2.90	14	1	<2	11	4	<.2	<.5	<.5	2	.02	.020	52	4	.04	44	.002	<1	.24	.001	.05	1	<1	1.2	1	<.01	<1
351384	<.2	32	16	105	.1	39	17	798	3.98	15	1	<2	8	8	<.2	<.5	<.5	13	.10	.043	32	19	.41	105	.005	<1	1.12	.006	.08	1	<1	2.1	1	<.01	2
351385	57.8	108	393	61	.5	39	20	783	5.00	48	3	<2	7	13	.2	.9	3.8	9	.13	.061	29	9	.09	91	.003	<1	.53	<.001	.05	2	<1	3.0	<1	.02	<1
351386	.7	41	114	81	.3	39	17	777	4.06	32	4	<2	5	20	<.2	<.5	1.0	21	.28	.066	28	24	.30	226	.008	<1	1.11	.002	.09	1	<1	3.6	<1	.02	2
STANDARD C3	26.8	64	35	169	5.3	35	11	795	3.37	59	24	2	21	30	22.6	16.5	22.3	81	.60	.095	22	178	.63	161	.087	20	1.78	.043	.17	15	2	4.8	<1	.03	6
STANDARD G-2	1.6	3	4	43	<.1	7	3	528	1.96	1	3	<2	5	82	<.2	<.5	<.5	38	.67	.097	10	78	.60	240	.121	1	1.00	.134	.52	2	<1	2.7	<1	<.01	4

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
- SAMPLE TYPE: SOIL SS80 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 17 2000 DATE REPORT MAILED: Oct 25/00 SIGNED BY: C. Leong .D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
351387	.3	23	35	54	.1	25	13	574	3.06	28	1	<2	9	11	<.2	.8	<.5	16	.16	.053	38	14	.26	89	.008	2	.74	.003	.07	2	<1	2.1	<1	<.01	2
351388	.4	49	36	77	.1	47	20	921	4.44	50	1	<2	16	13	<.2	.8	<.5	20	.15	.056	46	22	.36	99	.006	5	1.12	.006	.11	2	<1	4.4	<1	<.01	2
351389	2.8	34	25	32	.1	28	9	197	2.84	66	2	<2	13	7	<.2	.8	1.0	8	.08	.031	37	9	.14	43	.003	<1	.47	<.001	.04	2	<1	2.4	<1	<.01	1
351701	.4	43	28	83	.1	40	18	687	3.68	32	2	<2	10	114	<.2	<.5	.5	26	2.24	.062	25	22	.58	111	.014	5	1.09	.008	.11	1	<1	3.9	<1	.04	3
351702	1.2	44	44	80	.3	44	20	1146	4.34	52	1	<2	14	20	<.2	.7	1.3	23	.28	.061	34	17	.32	82	.006	4	.84	.004	.11	2	<1	3.8	<1	.02	2
351703	.4	27	26	59	<.1	30	13	485	3.04	26	1	<2	9	11	<.2	1.0	<.5	21	.15	.030	34	21	.35	89	.015	2	.91	.003	.07	2	<1	3.1	<1	<.01	2
351704	.4	42	51	69	.1	41	19	1046	3.99	49	2	<2	11	16	<.2	1.4	1.0	21	.23	.063	39	18	.30	95	.006	<1	.96	.003	.10	2	<1	3.9	1	<.01	2
351705	.5	30	41	62	<.1	34	16	520	3.52	44	1	<2	9	14	.2	.7	.7	21	.20	.048	38	20	.31	82	.004	1	1.08	.003	.07	3	<1	2.3	<1	<.01	2
351706	.6	32	39	66	.4	32	15	626	3.63	45	2	<2	8	14	.2	.9	.8	21	.22	.032	35	17	.29	71	.004	1	.92	.003	.06	2	<1	2.8	<1	<.01	2
351707	.6	40	31	68	.1	37	17	683	3.85	51	1	<2	11	10	<.2	.8	<.5	25	.14	.037	39	18	.34	76	.006	2	1.01	.004	.08	2	<1	3.3	<1	<.01	2
351708	.7	35	91	62	.1	31	15	577	3.49	49	1	<2	10	9	<.2	1.5	3.6	16	.11	.031	42	15	.26	57	.004	1	.81	.002	.06	2	<1	2.2	<1	<.01	1
351709	.2	37	31	77	.1	40	19	702	3.93	27	2	<2	10	12	<.2	1.2	<.5	30	.19	.050	40	26	.49	71	.013	<1	1.24	.003	.06	2	<1	3.7	<1	<.01	3
351710	.2	31	35	66	<.1	34	15	699	3.45	29	2	<2	11	10	<.2	.9	<.5	16	.11	.038	33	16	.26	84	.008	1	.85	.002	.10	2	<1	2.5	<1	.01	2
RE 351710	.4	31	35	67	<.1	34	15	703	3.45	30	2	<2	12	10	<.2	1.3	<.5	16	.11	.038	33	17	.27	87	.008	3	.86	.003	.10	2	<1	2.6	<1	.01	2
351711	.3	20	53	65	.1	24	10	269	3.36	26	1	<2	7	10	<.2	<.5	.5	21	.15	.039	30	17	.22	62	.004	2	1.06	.001	.05	2	<1	1.8	<1	<.01	2
351712	.3	26	51	75	.3	31	15	539	4.10	40	1	<2	8	12	<.2	.9	<.5	30	.15	.055	35	21	.27	75	.008	<1	1.11	.002	.07	2	<1	2.5	<1	<.01	2
351713	.8	39	40	77	.4	53	20	366	4.11	26	2	<2	10	11	<.2	.6	.6	30	.11	.056	29	26	.27	99	.017	1	1.39	.003	.07	2	<1	3.0	<1	.01	2
351714	.8	31	34	80	.1	31	13	286	3.95	42	1	<2	10	5	<.2	.6	.5	21	.04	.041	36	20	.26	60	.007	<1	1.15	.001	.04	2	<1	2.1	<1	<.01	2
351715	1.0	38	31	93	.1	41	19	433	4.23	31	1	<2	9	7	<.2	1.3	.5	35	.08	.047	37	33	.50	61	.011	<1	1.56	.003	.05	2	<1	2.8	<1	<.01	3
351716	.5	41	42	80	.2	42	20	1081	4.10	43	1	<2	10	7	<.2	.8	<.5	30	.06	.036	40	24	.47	67	.007	<1	1.41	.002	.06	3	<1	3.5	<1	<.01	3
351717	<.2	35	49	75	.3	38	16	658	3.55	45	2	<2	10	11	<.2	.9	.5	21	.15	.042	36	19	.36	96	.006	<1	1.03	.002	.06	2	<1	4.0	<1	<.01	2
351718	.3	40	69	72	.1	43	20	666	3.99	48	1	<2	8	9	<.2	.8	<.5	26	.11	.041	34	26	.37	100	.006	<1	1.30	.003	.08	4	<1	3.1	<1	<.01	2
351719	.6	34	33	80	.1	41	15	515	3.24	26	1	<2	7	13	<.2	.6	<.5	21	.17	.054	32	24	.33	126	.009	<1	1.04	.003	.07	1	<1	2.4	<1	<.01	2
351720	1.3	47	28	113	.2	63	18	402	4.93	25	2	<2	5	16	<.2	1.0	<.5	30	.21	.057	26	39	.40	218	.007	<1	1.58	.003	.09	1	<1	2.9	<1	.01	3
351721	.3	46	35	81	.1	45	20	1084	4.24	48	2	<2	12	15	<.2	.8	.5	26	.22	.066	37	23	.41	120	.012	4	1.11	.005	.11	2	<1	4.3	<1	<.01	2
351722	1.2	48	36	91	.3	51	18	698	3.53	35	2	<2	9	27	<.2	1.2	.6	19	.51	.062	24	22	.44	150	.016	1	.81	.004	.06	2	<1	3.3	<1	.02	2
351723	.5	39	31	80	.1	38	17	687	3.60	35	1	<2	10	55	<.2	.9	.5	22	1.04	.070	30	19	.47	82	.014	2	.87	.004	.07	1	<1	3.4	<1	.02	2
351724	.6	41	29	80	.1	38	17	697	3.53	29	2	<2	10	86	<.2	<.5	<.5	22	1.70	.070	28	20	.50	98	.019	6	.89	.006	.07	2	<1	3.7	<1	.02	2
351725	.5	40	30	79	.2	39	16	791	3.50	29	2	<2	10	23	<.2	.8	<.5	24	.36	.070	30	19	.42	92	.018	2	.80	.005	.05	1	<1	3.4	<1	.02	2
351727	1.5	38	30	83	.4	43	15	601	3.30	21	3	<2	7	16	<.2	1.3	<.5	21	.21	.057	27	19	.29	153	.012	4	.70	.002	.04	3	<1	2.5	<1	.02	1
351729	1.8	31	12	73	.1	36	13	442	2.83	12	1	<2	8	6	<.2	1.1	<.5	15	.05	.039	27	20	.20	80	.012	<1	.53	.001	.03	2	<1	1.9	<1	<.01	1
351730	1.6	45	22	98	.3	54	17	676	3.46	15	2	<2	8	20	<.2	.8	<.5	26	.25	.068	26	26	.42	204	.022	3	.92	.004	.06	1	<1	3.3	<1	.02	2
351731	.8	33	17	76	.2	40	11	660	2.81	14	2	<2	7	20	<.2	.9	<.5	17	.23	.066	24	14	.35	121	.013	<1	.54	.002	.04	1	<1	2.3	<1	<.01	1
351732	2.9	53	39	129	1.7	55	16	379	3.33	17	6	<2	4	24	.2	1.9	<.5	46	.25	.101	29	38	.37	450	.010	2	1.97	.005	.16	1	<1	5.0	<1	.02	4
STANDARD C3	27.9	67	38	175	5.5	37	12	810	3.40	60	24	3	22	30	23.6	17.5	24.1	83	.61	.096	22	186	.64	167	.088	25	1.89	.042	.17	15	1	5.0	<1	.03	7
STANDARD G-2	1.6	3	3	46	<.1	8	4	558	2.09	<1	3	<2	4	77	<.2	<.5	<.5	42	.69	.100	11	83	.63	242	.131	<1	.98	.088	.50	3	<1	2.9	<1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
351733	1.8	32	32	101	1.0	35	9	155	2.63	25	2	<2	4	17	<.2	1.2	<.5	31	.18	.081	29	24	.26	303	.006	3	1.25	.007	.11	1	<1	3.2	<1	.01	2
351734	1.7	26	24	97	.5	34	13	197	2.62	20	2	<2	6	17	<.2	1.0	<.5	26	.18	.063	31	25	.29	258	.007	2	1.16	.006	.11	2	<1	2.9	<1	<.01	3
351735	1.2	24	15	67	.2	23	9	444	2.40	16	1	<2	4	12	<.2	.7	<.5	18	.10	.040	30	20	.26	186	.008	<1	.88	.004	.08	1	<1	2.1	<1	<.01	2
351736	1.0	26	18	74	.2	26	11	373	2.69	19	1	<2	3	11	<.2	.6	<.5	22	.11	.046	33	21	.29	218	.007	3	1.06	.004	.10	2	<1	2.5	<1	<.01	2
351737	.4	41	28	81	.1	37	17	819	3.79	38	1	<2	9	12	<.2	.5	<.5	19	.11	.040	39	19	.28	218	.007	<1	1.02	.005	.12	2	<1	3.8	<1	<.01	2
351738	1.4	25	24	66	.2	25	11	443	3.06	24	1	<2	3	14	<.2	1.0	<.5	26	.12	.049	32	23	.32	215	.007	<1	1.05	.004	.09	2	<1	2.0	<1	<.01	2
351739	1.7	27	20	66	.9	25	9	340	3.52	25	1	<2	4	8	<.2	1.1	<.5	26	.06	.058	29	24	.29	135	.010	<1	.93	.003	.07	2	<1	1.8	<1	.01	2
351740	1.8	15	17	38	.5	15	4	207	2.65	10	1	<2	1	10	<.2	.7	<.5	22	.07	.072	22	18	.17	139	.008	2	.74	.002	.06	1	<1	1.0	<1	.02	2
351741	2.2	18	18	38	.9	14	5	227	2.80	18	1	<2	4	8	<.2	1.0	<.5	30	.04	.078	26	20	.16	101	.012	1	.78	.002	.06	1	<1	1.3	<1	.01	2
351742	1.8	17	17	39	.3	13	5	436	2.79	11	1	<2	2	7	<.2	.9	<.5	30	.03	.056	24	15	.10	114	.022	<1	.59	.002	.04	2	<1	1.2	<1	.01	3
351743	2.1	38	23	77	.5	32	10	423	3.09	17	2	<2	5	9	<.2	1.3	<.5	30	.06	.051	28	26	.29	152	.018	1	1.10	.003	.08	2	<1	2.7	<1	<.01	2
351744	1.5	19	17	40	.4	14	4	134	2.86	13	1	<2	3	8	<.2	1.1	<.5	30	.03	.050	23	22	.17	103	.010	<1	.93	.002	.05	1	<1	1.4	<1	.01	2
351745	.9	10	15	23	.9	7	1	67	1.69	5	<1	<2	2	5	<.2	<.5	<.5	21	.02	.039	22	15	.09	123	.008	1	.71	.001	.03	1	<1	1.0	1	<.01	3
351746	1.9	15	14	33	1.5	13	2	77	2.04	9	1	<2	2	5	<.2	.7	<.5	29	.02	.047	22	15	.10	111	.010	<1	.63	.001	.04	1	<1	1.0	<1	.01	2
351747	2.3	19	15	42	1.5	17	3	104	3.21	14	1	<2	2	8	<.2	1.4	<.5	30	.03	.179	21	24	.16	122	.010	2	.85	.002	.06	1	<1	1.0	<1	.02	2
351748	1.2	7	10	15	.3	5	1	56	1.47	4	<1	<2	2	4	<.2	<.5	<.5	21	.02	.048	22	11	.07	118	.009	<1	.50	<.001	.03	1	<1	.6	<1	<.01	2
351749	.8	27	19	78	.8	34	8	170	3.27	8	2	<2	3	15	<.2	<.5	<.5	26	.23	.055	22	55	.17	346	.004	<1	1.14	.002	.03	1	<1	2.2	<1	.02	3
351750	1.1	30	18	83	.5	32	8	178	4.09	10	2	<2	3	12	<.2	<.5	<.5	22	.17	.050	27	34	.23	238	.005	<1	1.06	.002	.03	1	<1	2.9	<1	.01	2
351851	.3	48	33	83	.2	41	19	774	3.74	32	2	<2	11	77	<.2	<.5	.5	27	1.49	.071	30	21	.52	85	.016	5	.92	.006	.07	2	<1	3.7	<1	.02	2
351852	.5	41	28	79	.2	39	17	718	3.63	40	2	<2	11	130	<.2	<.5	.7	23	2.39	.060	24	19	.45	85	.007	4	.92	.006	.11	1	<1	3.6	<1	.04	2
351853	1.0	15	15	41	.2	18	4	126	2.45	17	1	<2	5	12	<.2	<.5	<.5	23	.17	.027	34	20	.19	91	.005	<1	.82	.002	.04	1	<1	1.4	<1	<.01	3
351854	.5	20	22	56	.2	27	8	231	3.11	26	1	<2	6	14	<.2	<.5	<.5	22	.20	.044	31	24	.32	109	.006	<1	.99	.003	.06	1	<1	2.0	<1	<.01	2
351855	.3	31	46	68	.5	40	14	635	3.65	39	2	<2	5	18	<.2	<.5	.5	25	.28	.060	30	25	.35	155	.005	<1	1.16	.003	.07	2	<1	3.5	<1	.02	2
RE 351855	.3	31	46	67	.5	40	14	640	3.61	39	2	<2	5	18	<.2	.7	.6	22	.28	.059	30	25	.34	153	.004	1	1.14	.003	.07	2	<1	3.4	<1	.02	2
351856	.3	36	71	76	1.0	49	17	725	4.15	39	2	<2	7	13	<.2	.7	.7	24	.17	.054	35	29	.39	152	.005	<1	1.41	.003	.08	2	<1	4.6	<1	.01	3
351857	.3	22	27	57	.1	27	9	194	3.41	37	1	<2	7	6	<.2	<.5	<.5	22	.07	.027	34	22	.25	83	.003	<1	.94	.002	.04	2	<1	1.6	1	<.01	2
351858	.4	27	32	65	.1	35	13	214	3.10	37	1	<2	9	9	<.2	<.5	<.5	18	.12	.042	37	23	.30	119	.005	<1	.93	.002	.06	2	<1	2.4	<1	<.01	2
351859	.7	37	40	72	.1	44	19	637	4.01	51	1	<2	9	10	<.2	.9	.7	16	.13	.059	40	25	.26	127	.004	<1	1.04	.002	.06	2	<1	2.8	<1	<.01	2
351860	.4	28	23	72	.1	36	9	216	3.58	24	1	<2	7	8	<.2	<.5	<.5	26	.08	.038	30	28	.31	98	.010	<1	1.19	.003	.06	1	<1	2.0	<1	<.01	2
351861	.4	17	16	47	<.1	17	5	114	2.83	27	1	<2	7	4	<.2	<.5	<.5	23	.03	.039	30	18	.14	68	.009	2	.83	.001	.03	1	<1	1.4	<1	<.01	2
351862	<.2	21	24	59	.1	24	8	190	3.95	32	1	<2	5	8	<.2	<.5	<.5	26	.09	.043	28	25	.25	116	.006	<1	1.08	.003	.05	2	<1	1.7	<1	<.01	2
351863	1.0	24	24	73	.2	35	13	381	3.76	31	1	<2	6	8	<.2	.6	<.5	31	.10	.039	37	34	.44	100	.005	1	1.29	.003	.05	2	<1	2.2	1	<.01	3
351864	.6	30	51	87	.5	42	15	1115	3.96	26	2	<2	6	15	<.2	<.5	.6	31	.20	.056	32	33	.40	125	.004	<1	1.56	.004	.07	2	<1	3.4	1	.01	3
351865	.4	12	18	42	<.1	16	6	282	2.44	24	<1	<2	5	6	<.2	.8	.7	31	.06	.024	37	14	.08	83	.008	<1	.67	.002	.04	2	<1	1.3	1	<.01	3
STANDARD C3	28.3	69	36	173	5.7	37	12	816	3.46	60	25	3	23	30	23.6	17.8	23.6	87	.62	.099	22	185	.64	167	.088	21	1.81	.041	.17	16	1	4.8	<1	.03	7
STANDARD G-2	1.5	3	2	45	<.1	7	4	546	2.02	<1	3	<2	4	74	<.2	<.5	<.5	39	.66	.101	10	79	.62	234	.127	1	.90	.087	.49	3	<1	2.8	1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
351867	.3	25	38	61	.4	35	12	475	3.29	27	1	<2	6	12	<.2	<.5	.6	16	.17	.058	31	21	.29	72	.007	1	1.06	.008	.07	2	<1	2.6	<1	<.01	2
351868	.4	23	37	59	.4	28	12	387	3.34	26	1	<2	6	11	<.2	.9	.5	18	.15	.037	30	18	.24	74	.005	2	.98	.005	.07	2	<1	1.8	<1	<.01	2
351870	.3	36	46	71	.5	38	16	653	4.22	43	2	<2	7	18	<.2	.6	1.3	27	.26	.059	35	29	.36	91	.004	<1	1.46	.006	.10	2	<1	4.1	<1	.01	3
351871	.2	28	51	76	.1	36	17	522	3.69	49	1	<2	7	10	<.2	.5	.7	23	.13	.047	34	27	.41	72	.007	<1	1.17	.005	.07	2	<1	2.7	<1	<.01	2
351872	.4	17	21	55	.1	17	6	163	3.28	27	1	<2	8	4	<.2	<.5	<.5	24	.03	.035	32	20	.19	61	.005	1	.97	.003	.05	2	<1	1.5	<1	<.01	2
351873	2.2	15	15	43	.1	13	4	250	3.73	15	1	<2	5	7	<.2	1.0	<.5	32	.03	.101	26	24	.20	100	.011	<1	1.07	.002	.05	2	<1	1.4	<1	<.01	3
351874	1.7	25	21	68	.3	25	6	217	3.91	15	1	<2	4	8	<.2	1.4	<.5	29	.05	.077	20	34	.25	136	.014	<1	1.59	.004	.05	2	<1	2.3	<1	.02	2
351875	2.4	21	15	57	.4	20	5	167	3.06	13	1	<2	3	7	<.2	1.0	<.5	20	.05	.084	20	22	.15	92	.010	<1	1.04	.002	.03	1	<1	1.5	<1	.01	2
351877	6.8	45	21	109	.8	42	13	485	4.06	30	4	<2	6	12	<.2	3.3	<.5	35	.08	.105	25	25	.28	286	.020	<1	1.16	.004	.07	1	<1	2.9	<1	<.01	2
351878	2.3	18	15	92	2.7	26	5	127	2.18	13	4	<2	1	12	<.2	1.7	<.5	25	.08	.080	24	19	.25	328	.007	<1	.93	.004	.08	1	<1	1.6	<1	.01	2
351879	1.5	37	18	88	.3	34	12	420	3.22	17	2	<2	10	8	<.2	1.9	<.5	21	.04	.046	32	22	.37	197	.010	1	1.10	.003	.09	1	<1	2.6	1	<.01	2
351880	.9	49	35	109	.1	51	18	815	4.28	23	2	<2	10	11	<.2	1.4	.5	32	.09	.062	35	30	.49	281	.022	<1	1.50	.005	.11	1	<1	4.8	1	<.01	3
RE 351880	.9	48	35	108	.1	50	18	795	4.17	22	2	<2	11	9	<.2	1.0	<.5	32	.09	.061	34	30	.49	276	.022	<1	1.47	.009	.11	2	<1	4.7	1	<.01	3
351881	2.6	35	38	94	.3	36	22	937	4.76	38	3	<2	3	11	<.2	2.2	<.5	35	.10	.090	23	29	.32	213	.012	<1	1.29	.003	.09	2	<1	2.2	1	.01	3
351882	1.4	29	21	79	.3	30	14	564	3.15	32	2	<2	6	8	<.2	1.5	<.5	21	.06	.041	32	19	.28	149	.011	<1	.83	.003	.05	2	<1	2.1	2	<.01	2
351883	.8	38	31	91	.1	39	17	818	3.70	32	2	<2	8	12	<.2	1.0	<.5	21	.10	.043	35	22	.34	255	.012	1	1.10	.005	.10	2	<1	3.3	1	<.01	2
351884	2.4	33	25	130	.5	51	20	876	4.09	24	4	<2	2	13	<.2	1.3	<.5	29	.11	.082	23	36	.34	335	.006	<1	1.44	.005	.10	2	<1	2.7	1	.01	3
351885	.4	42	30	82	.1	40	18	829	3.84	40	2	<2	11	19	<.2	.7	<.5	21	.21	.059	36	21	.33	197	.011	1	1.05	.008	.13	2	<1	3.9	<1	<.01	2
351886	.4	56	27	108	.2	52	21	828	4.24	16	2	<2	9	21	<.2	1.1	.6	33	.25	.071	28	32	.52	181	.028	<1	1.26	.006	.08	1	<1	4.9	<1	<.01	3
351887	.4	47	35	97	.2	44	21	799	4.16	37	2	<2	11	20	<.2	.8	.7	25	.24	.070	37	26	.42	217	.015	1	1.20	.008	.13	2	<1	4.4	<1	<.01	3
351889	.8	41	26	97	.3	46	17	774	3.50	18	4	<2	9	18	.2	1.1	<.5	22	.16	.064	29	21	.29	136	.027	1	.81	.005	.05	1	<1	3.2	<1	<.01	2
351890	.5	43	22	230	.1	103	19	1525	3.91	14	6	<2	12	11	1.1	<.5	<.5	7	.10	.060	32	5	.11	91	.001	1	.59	.003	.04	1	<1	1.5	1	<.01	<1
351891	1.1	68	40	156	.1	91	57	1945	3.74	16	7	<2	9	10	.6	.7	.5	22	.04	.056	24	21	.32	169	.028	<1	1.28	.003	.06	2	<1	3.6	2	<.01	2
351892	.3	39	27	111	.1	60	25	1644	3.89	14	4	<2	13	8	.4	.6	<.5	5	.05	.063	37	6	.06	128	.002	<1	.41	.001	.04	2	<1	1.9	1	<.01	<1
351893	.3	36	19	96	.1	62	20	1087	3.39	12	3	<2	11	7	.3	<.5	<.5	7	.05	.047	30	15	.14	88	.004	<1	.43	.004	.03	1	<1	1.8	1	<.01	1
351895	.9	41	26	86	.2	45	17	544	3.50	22	2	<2	7	22	.2	1.2	<.5	26	.33	.065	22	24	.39	138	.030	<1	.85	.008	.05	1	<1	3.2	<1	.01	2
351897	.5	36	31	70	.2	36	15	727	3.28	31	1	<2	8	15	<.2	1.1	.5	19	.22	.068	26	14	.28	68	.021	<1	.54	.005	.03	3	<1	2.5	<1	.02	1
351898	.6	38	28	77	.1	38	16	619	3.29	26	2	<2	8	95	.2	<.5	.6	24	1.82	.078	24	18	.46	103	.021	5	.75	.006	.05	1	<1	3.1	<1	.04	2
351899	.7	41	18	85	.1	47	16	571	3.11	14	2	<2	7	37	.2	.6	<.5	31	.50	.071	23	27	.49	151	.051	2	.99	.015	.07	1	<1	3.5	<1	<.01	3
351900	.4	33	29	83	.2	36	16	400	3.29	26	2	<2	9	27	<.2	<.5	.9	19	.45	.076	32	22	.47	115	.012	<1	1.01	.006	.07	1	<1	3.0	<1	.02	2
351901	.6	23	23	74	1.0	29	6	147	1.71	11	2	<2	2	19	<.2	<.5	<.5	17	.22	.061	25	21	.29	424	.006	<1	1.09	.004	.09	1	<1	2.2	<1	.03	2
351902	1.1	23	24	66	1.2	27	11	264	2.00	19	3	<2	2	24	.2	.6	<.5	21	.30	.073	23	22	.28	443	.005	<1	1.09	.005	.08	1	<1	2.2	<1	.04	2
351903	1.6	36	24	72	.4	36	16	390	2.74	17	3	<2	4	19	.2	.8	<.5	24	.20	.062	24	20	.28	321	.010	4	.88	.005	.05	1	<1	2.6	<1	.03	2
351904	1.4	42	23	105	.6	63	18	692	2.58	15	4	<2	5	17	.3	1.0	<.5	28	.17	.069	24	25	.31	239	.028	<1	1.04	.005	.06	1	<1	3.2	<1	.02	2
STANDARD C3	27.3	64	35	169	5.3	36	11	791	3.30	58	24	3	22	29	23.2	18.2	24.0	81	.59	.095	22	178	.61	162	.085	20	1.83	.041	.17	15	1	4.7	<1	.03	7
STANDARD G-2	1.7	3	3	46	<.1	8	4	564	2.08	<1	3	<2	4	78	<.2	<.5	<.5	40	.69	.105	11	83	.63	248	.128	<1	1.00	.099	.52	2	<1	2.8	1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
351905	1.0	39	19	95	.2	48	15	550	2.97	13	3	<2	9	13	<.2	<.5	<.5	16	.12	.059	30	17	.23	165	.019	2	.72	.004	.05	1	<1	2.9	1	.01	2
351906	.8	55	22	106	.3	77	22	1871	4.68	13	4	<2	7	26	<.2	.8	.5	13	.30	.079	27	15	.19	244	.007	3	.68	.011	.07	1	<1	3.5	<1	.03	1
351908	1.2	43	27	105	.2	47	16	584	3.45	16	3	<2	8	21	.2	<.5	<.5	25	.29	.070	27	24	.40	158	.026	4	.88	.006	.05	1	<1	3.2	<1	.02	2
351909	1.4	36	25	111	.2	46	13	604	3.39	12	4	<2	8	12	<.2	.6	<.5	13	.13	.059	24	17	.26	138	.013	3	.67	.003	.04	2	<1	2.6	<1	.02	1
351910	2.5	44	22	114	.3	57	15	696	3.43	14	5	<2	6	16	.3	1.0	<.5	16	.18	.064	23	23	.32	167	.010	1	.63	.003	.04	2	<1	2.6	<1	.03	1
351911	.5	39	32	83	.1	41	17	623	3.61	36	2	<2	9	52	<.2	.8	.5	16	.97	.081	29	17	.38	92	.018	1	.68	.004	.05	2	<1	3.2	<1	.02	2
351912	.7	48	30	99	.2	51	20	672	3.69	27	2	<2	9	54	.2	<.5	<.5	25	1.01	.074	28	25	.51	162	.023	4	1.06	.010	.11	2	<1	3.9	<1	.01	2
351913	.2	49	31	95	.1	43	20	839	4.08	32	2	<2	10	116	<.2	<.5	<.5	28	2.46	.070	25	26	.69	117	.017	2	1.29	.014	.14	2	<1	4.4	<1	.05	3
351914	.5	41	25	85	.1	47	15	522	3.57	20	2	<2	10	18	<.2	<.5	<.5	25	.21	.060	34	28	.39	214	.016	2	1.24	.007	.13	1	<1	4.2	<1	<.01	3
351915	.4	36	50	65	.1	38	15	558	3.51	42	1	<2	8	10	<.2	<.5	<.5	19	.13	.031	35	24	.33	157	.007	3	1.16	.006	.10	2	<1	3.6	<1	<.01	2
351916	.4	41	35	78	.7	43	18	535	3.95	50	1	<2	9	7	<.2	<.5	.6	19	.05	.043	38	26	.35	118	.010	3	1.31	.006	.11	4	<1	3.2	<1	<.01	2
351917	.4	39	47	72	.2	38	15	676	3.79	52	2	<2	10	12	<.2	.7	.7	16	.17	.061	39	19	.29	87	.007	2	.92	.006	.09	2	<1	3.6	<1	<.01	2
351918	.7	39	48	81	.4	45	17	855	4.09	47	2	<2	7	14	<.2	<.5	.8	19	.21	.063	32	23	.32	107	.005	6	1.09	.004	.08	2	<1	3.7	<1	.01	2
351919	.4	48	49	87	1.1	51	19	919	4.72	45	3	<2	6	19	<.2	.9	.5	23	.30	.087	31	27	.34	130	.006	<1	1.34	.006	.09	2	<1	4.9	<1	.02	2
351920	<.2	29	33	68	.1	34	15	625	3.33	30	2	<2	8	13	<.2	<.5	<.5	22	.17	.054	35	25	.38	100	.013	4	1.10	.006	.09	2	<1	3.1	<1	<.01	2
RE 351920	.2	27	31	67	.1	33	14	603	3.15	28	1	<2	7	12	<.2	<.5	<.5	19	.16	.054	32	24	.36	91	.012	3	1.02	.004	.08	1	<1	2.9	<1	<.01	2
351921	.2	30	30	77	.2	43	18	611	3.71	30	2	<2	9	11	<.2	.5	<.5	25	.16	.040	37	31	.49	65	.013	1	1.20	.005	.07	2	<1	3.5	<1	<.01	3
351922	.4	50	49	97	.8	55	22	628	4.92	33	2	<2	9	17	<.2	.6	.6	30	.25	.069	34	29	.48	98	.010	2	1.44	.004	.09	3	<1	5.8	<1	.01	3
351923	.3	28	29	76	.1	35	17	543	3.90	20	1	<2	7	14	<.2	<.5	<.5	32	.21	.048	36	28	.55	65	.015	5	1.32	.005	.06	1	<1	2.8	<1	<.01	3
351924	.4	28	32	70	.5	38	14	489	3.60	27	2	<2	9	10	<.2	<.5	<.5	22	.14	.032	38	24	.44	62	.009	2	1.21	.004	.07	2	<1	3.3	<1	<.01	3
351925	.2	26	43	63	.2	25	11	453	3.24	27	1	<2	8	6	<.2	<.5	.6	13	.04	.036	34	15	.22	69	.006	3	.91	.003	.07	2	<1	1.9	1	<.01	2
351926	.2	34	55	73	.1	34	15	679	3.54	50	2	<2	10	14	<.2	<.5	<.5	16	.17	.059	39	18	.31	72	.009	4	1.01	.008	.12	2	<1	3.1	<1	<.01	2
351927	.2	24	36	69	<.1	26	9	271	3.66	22	1	<2	7	6	<.2	<.5	<.5	13	.04	.040	30	19	.23	78	.005	2	1.08	.002	.07	2	<1	1.7	<1	.01	2
351928	.5	35	60	84	.6	36	19	1042	4.44	41	3	<2	6	14	.2	<.5	1.5	20	.21	.073	27	21	.25	87	.007	<1	1.18	.004	.08	2	<1	3.5	<1	.01	2
351930	2.5	37	18	84	.4	32	7	199	2.92	18	2	<2	5	12	<.2	1.6	<.5	26	.04	.052	24	27	.22	191	.014	3	1.38	.002	.09	1	<1	2.1	<1	.01	2
351931	2.0	16	12	55	.5	20	3	93	2.76	10	1	<2	6	9	<.2	.5	<.5	20	.07	.045	26	22	.23	172	.011	3	.96	.001	.05	1	<1	1.6	<1	<.01	2
351932	2.9	18	17	66	.4	23	7	311	2.64	15	1	<2	3	14	<.2	.6	<.5	29	.13	.042	27	24	.25	620	.010	4	.89	.003	.07	1	<1	1.5	<1	<.01	2
351933	2.6	23	14	49	.8	19	4	122	2.82	15	1	<2	6	10	<.2	1.2	<.5	20	.05	.037	28	21	.22	172	.011	3	.93	.001	.07	1	<1	1.7	<1	<.01	2
351934	.6	40	23	85	<.1	38	15	520	3.66	15	2	<2	10	7	<.2	.7	<.5	19	.03	.041	36	22	.35	212	.012	2	1.19	.005	.13	2	<1	3.1	<1	<.01	2
351935	.8	17	14	49	.1	20	5	144	2.32	10	1	<2	5	6	<.2	.8	<.5	14	.03	.039	31	16	.24	107	.010	2	.82	.001	.06	1	<1	1.5	<1	<.01	2
351937	2.4	34	20	67	.2	28	10	353	2.84	18	2	<2	9	8	<.2	1.6	<.5	22	.04	.052	30	18	.20	138	.017	4	.72	.001	.05	1	<1	2.1	<1	<.01	1
351938	.9	37	25	79	.2	40	13	611	3.31	22	2	<2	10	15	<.2	.7	<.5	20	.16	.057	34	23	.33	189	.017	3	.98	.005	.10	2	<1	3.3	<1	<.01	2
351939	.9	38	32	84	.2	42	16	795	3.32	22	2	<2	9	17	.2	1.2	<.5	20	.20	.066	33	18	.28	157	.015	4	.76	.003	.07	2	<1	2.9	<1	.01	2
351940	<.2	41	23	149	<.1	78	31	1313	4.11	7	4	<2	13	9	.4	1.0	<.5	3	.05	.054	34	10	.04	151	.001	4	.27	.002	.05	2	<1	2.1	1	<.01	<1
STANDARD C3	27.5	65	36	172	5.4	36	11	799	3.35	59	26	2	22	31	23.4	18.3	23.9	79	.60	.098	22	179	.63	163	.084	23	1.85	.044	.18	15	1	4.9	<1	.03	6
STANDARD G-2	1.5	2	3	47	<.1	7	4	548	2.03	<1	3	<2	4	78	<.2	<.5	<.5	39	.68	.107	11	84	.62	247	.125	4	.99	.102	.50	3	<1	2.7	<1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
351941	.3	36	23	117	.1	56	18	1156	4.30	17	5	<2	12	11	.2	1.3	<.5	2	.04	.063	32	6	.06	136	.001	1	.35	.001	.04	1	<1	2.1	1	<.01	<1
351942	1.1	42	18	91	.1	46	15	463	3.20	11	2	<2	8	17	.2	1.3	<.5	36	.19	.062	29	26	.38	177	.060	1	1.07	.007	.05	1	<1	4.0	<1	<.01	3
351943	1.2	40	34	95	.2	47	17	841	3.55	22	2	<2	9	15	.2	1.3	<.5	16	.16	.062	29	18	.25	155	.015	3	.64	.003	.05	1	<1	2.7	<1	.01	1
351944	1.1	43	42	98	.3	51	18	947	3.84	23	2	<2	10	17	.2	1.3	<.5	19	.20	.066	32	20	.30	182	.014	<1	.75	.005	.06	1	<1	3.1	<1	.01	1
351947	2.1	41	19	87	.4	42	12	502	3.03	15	3	<2	6	14	.3	1.8	<.5	21	.18	.065	21	17	.25	261	.023	1	.55	.002	.03	1	<1	2.6	<1	.02	1
351948	1.9	41	21	104	.3	52	15	598	3.54	14	4	<2	7	14	.2	1.4	<.5	16	.16	.060	22	21	.30	169	.012	<1	.59	.001	.03	1	<1	2.5	<1	.03	1
351949	.5	36	51	72	.1	35	16	741	3.49	34	2	<2	9	83	<.2	.6	<.5	16	1.56	.079	28	16	.41	67	.017	<1	.69	.005	.05	1	<1	3.3	<1	.02	2
351950	.5	43	31	82	.2	39	18	739	3.78	31	2	<2	10	82	<.2	.5	.5	24	1.56	.077	29	20	.49	82	.019	2	.90	.007	.08	1	<1	3.7	<1	.02	2
351951	.4	35	40	87	.4	35	16	694	4.42	38	2	<2	5	17	<.2	1.0	.5	26	.28	.057	33	23	.28	90	.006	<1	1.17	.004	.08	1	<1	3.4	<1	.01	3
351952	.3	28	43	75	<.1	35	17	525	4.03	41	1	<2	10	12	<.2	.8	<.5	27	.19	.051	43	26	.47	80	.006	<1	1.17	.004	.07	1	<1	2.9	<1	<.01	3
351953	<.2	35	41	67	.3	38	15	693	4.20	37	2	<2	6	14	<.2	.7	<.5	27	.24	.055	33	27	.41	94	.007	2	1.20	.003	.07	2	<1	4.0	<1	.01	3
351954	.4	24	101	78	.3	29	10	273	4.24	29	1	<2	5	10	<.2	.9	1.0	23	.12	.061	28	23	.25	225	.005	<1	1.19	.003	.08	1	<1	2.0	<1	.01	2
351957	.3	37	59	70	.1	38	16	280	4.19	48	1	<2	12	6	<.2	1.0	1.2	21	.05	.035	36	22	.28	99	.005	<1	1.12	.003	.06	1	<1	2.4	<1	<.01	2
351958	.2	37	38	87	.1	46	20	379	3.99	45	1	<2	11	5	<.2	.9	<.5	27	.05	.038	32	29	.39	113	.011	<1	1.49	.005	.10	2	<1	3.0	<1	<.01	2
351959	.2	13	21	39	.5	11	4	178	2.87	20	<1	<2	5	5	<.2	<.5	<.5	27	.05	.034	26	19	.13	81	.007	<1	1.07	.003	.05	1	<1	1.4	1	.01	3
351960	.5	38	29	94	.5	52	14	318	4.14	28	1	<2	5	8	<.2	.9	<.5	23	.08	.054	28	32	.37	171	.005	<1	1.46	.003	.09	2	<1	2.8	1	.01	2
351961	.3	45	41	86	.8	57	19	1078	4.47	36	3	<2	6	21	<.2	.9	.7	27	.29	.070	30	32	.42	195	.006	1	1.65	.006	.12	2	<1	5.2	<1	.02	3
351962	.3	19	28	60	.1	22	8	231	3.86	31	1	<2	6	8	<.2	.7	<.5	25	.10	.044	31	24	.28	101	.007	<1	1.04	.002	.07	2	<1	1.7	1	<.01	2
351963	.3	33	32	77	.1	35	15	442	3.75	38	1	<2	9	5	<.2	.9	<.5	24	.05	.032	35	24	.34	96	.007	<1	1.13	.002	.07	1	<1	2.4	<1	<.01	2
351965	.2	36	34	97	.1	51	18	287	4.49	38	1	<2	11	4	<.2	.8	<.5	27	.04	.040	32	36	.38	128	.008	<1	1.62	.003	.09	2	<1	3.2	1	<.01	3
RE 351965	<.2	36	33	97	<.1	51	18	289	4.46	37	1	<2	11	5	<.2	.8	<.5	27	.04	.040	31	36	.39	126	.008	<1	1.62	.003	.09	2	<1	3.2	1	<.01	2
351966	.4	27	22	66	.2	31	11	406	3.73	31	1	<2	4	15	<.2	.9	<.5	24	.23	.058	33	27	.27	136	.006	<1	1.07	.004	.07	1	<1	2.6	1	.01	2
351967	.3	32	35	79	.5	42	20	983	4.95	47	2	<2	4	24	<.2	.9	.7	27	.40	.077	25	27	.35	156	.005	<1	1.20	.005	.09	2	<1	4.0	<1	.02	2
351968	.5	49	30	93	.1	46	20	798	4.26	22	2	<2	11	98	<.2	<.5	<.5	29	2.09	.070	27	29	.69	122	.018	2	1.34	.010	.12	1	<1	4.3	<1	.03	3
351969	.4	42	32	82	.2	41	18	769	3.86	38	2	<2	10	91	<.2	<.5	.6	21	1.75	.071	30	22	.50	106	.014	<1	1.02	.009	.11	1	<1	3.8	<1	.02	2
351970	.5	40	36	76	.2	42	18	798	3.90	50	2	<2	11	72	<.2	.8	<.5	19	1.41	.075	35	20	.39	84	.012	<1	.85	.006	.10	2	<1	3.8	<1	.02	2
351973	2.0	39	20	95	.3	44	14	499	3.19	14	3	<2	7	14	.2	1.3	<.5	23	.17	.064	29	19	.29	185	.024	2	.61	.003	.03	1	<1	2.5	1	.02	1
351975	1.4	30	19	83	.2	38	14	548	3.16	13	3	<2	7	12	<.2	1.2	<.5	17	.09	.056	26	16	.22	126	.015	2	.52	.003	.03	1	<1	1.9	<1	.01	1
351976	2.3	49	21	110	.7	54	19	685	3.44	15	4	<2	5	21	.2	1.6	<.5	24	.25	.067	23	24	.37	410	.021	5	.82	.005	.05	1	<1	3.6	<1	.02	2
351977	2.3	44	19	108	.5	52	16	527	3.32	14	3	<2	7	16	<.2	1.0	<.5	24	.18	.059	24	23	.38	271	.024	1	.87	.004	.05	1	<1	3.2	<1	.01	2
351978	1.9	42	20	101	.5	49	15	584	3.28	15	3	<2	6	21	.2	1.2	<.5	21	.29	.068	26	22	.39	315	.020	2	.77	.003	.05	1	<1	3.1	<1	.02	2
351979	1.2	36	17	94	.2	46	15	638	3.15	13	3	<2	8	8	.2	1.1	<.5	21	.06	.043	27	20	.28	132	.025	2	.75	.001	.03	1	<1	2.9	<1	<.01	1
351980	1.3	43	24	105	.4	49	16	478	3.43	15	3	<2	7	19	<.2	1.5	<.5	28	.17	.067	29	27	.43	202	.023	<1	1.09	.004	.07	1	<1	4.0	<1	<.01	2
351981	1.0	41	22	94	.3	44	16	696	3.31	13	2	<2	7	17	.2	.9	<.5	28	.20	.068	29	25	.41	215	.023	1	.92	.005	.06	1	<1	3.4	<1	<.01	2
STANDARD C3	27.9	68	38	176	5.5	37	12	828	3.51	60	24	3	23	30	23.9	17.7	23.5	84	.63	.099	23	183	.64	167	.088	21	1.81	.043	.17	14	2	4.8	<1	.03	6
STANDARD G-2	1.5	3	3	46	<.1	7	4	559	2.08	<1	3	<2	4	80	<.2	<.5	<.5	41	.69	.103	10	82	.62	246	.132	1	.96	.104	.51	2	<1	2.8	2	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004087R Page 1

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: K. Ross

SAMPLE#	Au* ppb
351351	3.8
351352	8.7
351353	3.5
351354	51.8
351355	11.8
351356	60.9
351357	15.1
351358	23.1
351359	200.3
351362	217.0
351363	157.4
351364	365.1
351365	32.1
RE 351365	27.7
351366	76.5
351367	154.1
351368	31.8
351369	85.7
351370	197.0
351371	28.6
351372	51.6
351373	6.6
351374	38.4
351375	8.9
351376	171.7
351377	174.6
351378	91.0
351379	33.3
351381	39.4
351382	4.0
351383	1.4
351384	3.0
351385	27.0
351386	55.9
STANDARD DS2	189.1

AU* BY ACID LEACHED, ANALYSIS BY ICP/MS. (10 gm)
- SAMPLE TYPE: SOIL PULP
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: NOV 23 2000 DATE REPORT MAILED: Nov 27/00 SIGNED BY: C. Leong D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au* ppb
351387	28.5
351388	27.0
351389	179.3
351701	11.6
351702	70.3
351703	21.6
351704	47.9
351705	147.8
351706	152.9
351707	40.7
351708	43.8
351709	16.7
351710	43.2
RE 351710	50.4
351711	55.3
351712	93.3
351713	49.4
351714	47.7
351715	599.1
351716	24.0
351717	46.5
351718	48.6
351719	145.1
351720	15.8
351721	212.5
351722	42.9
351723	18.8
351724	31.5
351725	37.4
351727	33.4
351729	16.1
351730	8.5
351731	4.3
351732	10.3
STANDARD DS2	196.4

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au* ppb
351733	17.1
351734	9.6
351735	8.6
351736	6.7
351737	12.6
351738	15.4
351739	19.0
351740	2.5
351741	43.0
351742	4.9
351743	12.4
351744	16.3
351745	6.5
351746	1.4
351747	8.7
351748	2.0
351749	6.7
351750	5.6
351851	63.8
351852	98.6
351853	28.1
351854	28.9
351855	30.4
RE 351855	86.6
351856	37.3
351857	76.3
351858	192.7
351859	41.2
351860	15.9
351861	13.6
351862	38.7
351863	30.3
351864	24.3
351865	44.6
STANDARD DS2	191.6

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Date ___ FA ___

SAMPLE#	Au* ppb
351867	87.9
351868	18.2
351870	42.3
351871	49.5
351872	62.5
351873	3.1
351874	17.7
351875	11.1
351877	8.8
351878	4.4
351879	12.4
351880	18.7
RE 351880	7.0
351881	6.5
351882	13.4
351883	11.9
351884	9.9
351885	23.2
351886	6.0
351887	20.4
351889	48.8
351890	1.2
351891	7.2
351892	2.4
351893	4.7
351895	14.8
351897	206.7
351898	31.8
351899	16.3
351900	23.1
351901	7.7
351902	12.8
351903	22.3
351904	8.2
STANDARD DS2	200.1

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data__ FA ___

SAMPLE#	Au* ppb
351905	10.9
351906	6.1
351908	154.3
351909	41.9
351910	3.8
351911	81.6
351912	32.6
351913	14.7
351914	12.6
351915	23.1
351916	41.1
351917	51.2
351918	34.5
351919	30.3
351920	361.8
RE 351920	65.0
351921	15.0
351922	24.9
351923	17.3
351924	25.7
351925	19.9
351926	22.6
351927	31.8
351928	41.4
351930	13.5
351931	5.0
351932	2.5
351933	99.6
351934	8.3
351935	28.3
351937	6.2
351938	12.7
351939	344.3
351940	.8
STANDARD DS2	190.4

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ___

SAMPLE#	Au* ppb
351941	1.4
351942	8.5
351943	25.2
351944	4.7
351947	4.8
351948	21.9
351949	43.8
351950	26.7
351951	27.9
351952	14.8
351953	338.4
351954	27.2
351957	104.2
351958	113.8
351959	45.4
351960	13.2
351961	20.2
351962	57.3
351963	35.4
351965	25.6
RE 351965	19.7
351966	15.9
351967	29.3
351968	8.5
351969	23.8
351970	58.9
351973	6.3
351975	19.9
351976	17.9
351977	11.8
351978	11.8
351979	1720.5
351980	13.5
351981	7.3
STANDARD DS2	194.8

Sample type: SOIL [illegible]ULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confiden[illegible]l property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Date___ FA ___

SAMPLE#	Au* ppb
351983	10.4
351984	160.1
351985	4.0
351986	19.7
351987	11.9
351988	8.2
351989	12.1
351990	3.9
351991	1.5
351992	3.3
351994	34.1
351995	5.7
RE 351995	16.3
351996	10.2
351997	11.4
351998	19.9
351999	11.6
352000	20.0
STANDARD DS2	199.8

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)

(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004088 Page 1

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
351390	.6	24	23	72	.1	31	1	512	3.59	22	2	<2	4	13	<.2	1.0	.5	24	.20	.046	23	22	.28	120	.009	1	1.07	.005	.06	<1	<1	1.7	1	.01	3
351391	3.6	58	31	105	.2	54	2	420	5.01	35	4	<2	2	15	<.2	.8	1.3	18	.23	.066	17	17	.14	110	.004	1	.85	.005	.06	1	<1	1.8	<1	.02	2
351392	1.7	86	35	57	.3	42	1	251	5.05	71	2	<2	5	6	<.2	1.6	3.4	10	.05	.058	15	14	.10	69	.003	1	.49	.003	.05	<1	<1	1.5	1	.02	2
351393	1.3	59	31	65	.5	48	2	720	3.92	35	6	<2	4	21	.2	1.0	1.8	18	.35	.094	26	22	.26	199	.005	2	1.23	.006	.08	<1	<1	5.4	1	.02	3
351394	.6	46	25	74	.1	51	2	2035	4.30	50	1	<2	10	49	<.2	.8	.5	24	1.11	.071	32	26	.54	106	.009	1	1.20	.007	.12	<1	<1	3.8	2	<.01	3
351395	.9	24	33	65	.1	28	1	541	3.63	33	2	<2	6	14	<.2	.9	.7	23	.20	.067	27	22	.34	70	.005	<1	1.10	.005	.07	<1	<1	2.7	2	.01	4
351396	.9	29	37	75	.2	33	1	922	4.01	33	3	<2	7	18	<.2	.7	.9	23	.28	.073	27	23	.33	86	.006	<1	1.22	.005	.09	<1	<1	3.0	1	.01	4
351397	.6	29	34	73	.2	33	1	858	4.28	34	2	<2	5	16	<.2	1.4	.9	25	.25	.077	24	24	.33	89	.008	1	1.19	.005	.08	<1	<1	2.9	<1	.01	3
351398	.5	27	24	84	<.1	30	1	248	4.95	25	2	<2	7	6	<.2	2.1	.6	32	.06	.058	30	32	.43	62	.007	<1	1.58	.004	.05	1	<1	1.9	<1	.01	5
351399	.7	30	31	72	.3	32	1	397	3.77	33	1	<2	5	7	<.2	.8	.7	20	.06	.058	30	22	.28	87	.004	<1	1.10	.005	.05	1	<1	1.6	1	.01	3
351400	.6	23	19	60	.1	21	1	224	3.23	28	1	<2	7	3	<.2	1.1	.8	17	.02	.041	31	18	.21	49	.004	3	1.06	.004	.04	1	<1	1.4	1	<.01	3
351401	.5	38	33	71	1.2	35	1	425	3.41	40	2	<2	9	3	<.2	.8	.6	13	.02	.035	39	16	.25	37	.003	<1	.89	.004	.05	1	<1	1.7	<1	<.01	3
351403	.5	35	34	89	<.1	41	1	356	4.03	30	1	<2	7	6	.3	1.1	.7	24	.06	.046	31	28	.42	64	.007	<1	1.45	.004	.05	<1	<1	2.1	1	<.01	4
351404	.5	31	35	70	.2	35	1	652	3.76	26	2	<2	6	12	<.2	.8	.5	26	.16	.052	30	25	.37	93	.004	1	1.37	.005	.08	<1	<1	3.0	1	<.01	4
351405	.7	19	24	46	<.1	18	1	203	3.27	18	1	<2	2	7	<.2	.6	.6	27	.06	.053	23	17	.15	76	.009	1	.76	.005	.04	<1	<1	1.1	<1	.01	4
RE 351405	.7	18	24	47	<.1	18	1	205	3.25	17	1	<2	2	7	<.2	1.1	.5	25	.06	.052	24	17	.15	75	.008	4	.76	.005	.04	<1	<1	1.0	<1	.01	4
351406	.6	28	23	71	<.1	32	1	257	3.84	23	1	<2	5	9	<.2	1.4	<.5	24	.11	.046	27	28	.33	120	.009	1	1.32	.005	.08	<1	<1	1.9	2	<.01	4
351407	.7	35	32	81	.1	37	1	428	3.47	34	1	<2	5	7	.2	.8	.7	22	.08	.046	31	24	.30	113	.007	<1	1.29	.005	.08	1	<1	2.5	<1	<.01	4
351408	.7	16	22	45	<.1	13	1	111	2.51	16	1	<2	4	5	<.2	.6	.5	24	.04	.029	29	16	.16	101	.006	2	1.05	.004	.05	1	<1	1.7	1	<.01	5
351409	.8	30	33	67	<.1	30	1	373	3.77	38	1	<2	7	8	<.2	1.0	.8	18	.08	.036	31	19	.26	81	.004	1	.98	.005	.07	2	<1	1.7	<1	<.01	3
351410	.7	37	39	84	.2	40	1	801	4.18	37	2	<2	6	13	<.2	1.1	.9	24	.19	.065	29	26	.33	106	.006	4	1.28	.007	.09	1	<1	3.0	2	.01	4
351411	.7	36	36	77	.3	39	1	757	3.84	31	2	<2	4	17	.2	1.1	.9	24	.25	.074	26	24	.35	112	.005	1	1.34	.007	.09	<1	<1	3.4	<1	.02	4
351412	.6	34	36	74	<.1	36	1	500	3.46	38	2	<2	5	13	<.2	.9	.6	19	.17	.054	31	20	.29	93	.005	1	.99	.005	.08	1	<1	2.7	<1	.01	3
351413	.6	31	35	72	.2	33	1	478	3.51	38	1	<2	7	14	<.2	1.0	.8	19	.19	.051	30	19	.27	86	.006	1	.93	.006	.07	1	<1	2.8	2	<.01	3
351414	.6	58	32	103	.1	47	2	815	4.17	20	1	<2	9	60	.2	.8	<.5	34	1.36	.071	26	32	.72	93	.019	3	1.37	.009	.09	<1	<1	4.0	1	.02	5
351415	.7	42	39	78	.2	43	1	826	3.82	42	1	<2	10	28	<.2	.8	1.5	20	.51	.071	28	20	.41	71	.011	4	.83	.006	.07	1	<1	3.2	<1	.03	3
351416	.6	50	38	83	<.1	62	1	903	4.20	42	2	<2	9	23	<.2	.7	.9	35	.30	.081	28	46	.57	335	.017	1	1.00	.006	.06	1	1	4.6	1	.02	4
351417	.8	39	241	69	.7	43	1	589	4.07	61	2	<2	7	14	<.2	1.4	2.0	18	.23	.069	19	24	.29	58	.014	<1	.59	.005	.04	2	1	2.9	<1	.14	2
351419	.8	45	32	82	<.1	59	1	872	4.14	33	2	<2	6	27	<.2	1.2	.7	22	.44	.079	21	35	.38	89	.006	1	.75	.005	.05	<1	<1	3.3	1	.03	3
351420	.9	40	46	80	.2	45	1	792	3.93	30	3	<2	7	16	<.2	1.1	.6	13	.23	.061	17	12	.21	65	.015	1	.50	.005	.04	1	<1	2.3	2	.07	1
351421	1.2	48	42	93	1.0	50	2	797	4.14	33	2	4	8	24	<.2	.8	.5	24	.33	.069	24	21	.36	101	.025	2	.94	.007	.07	<1	<1	3.5	<1	.02	3
351422	.6	40	40	87	.1	44	1	749	3.67	29	2	<2	8	33	<.2	<.5	<.5	16	.54	.063	23	15	.32	82	.010	1	.66	.006	.06	<1	<1	2.7	<1	.04	2
351423	.7	45	33	85	.2	46	1	655	3.78	39	1	<2	9	84	<.2	.7	.7	24	2.05	.061	22	26	.52	146	.012	3	1.12	.009	.17	<1	<1	3.8	2	.02	4
351424	1.1	31	28	72	.1	32	1	146	3.41	34	2	<2	8	9	<.2	1.3	<.5	23	.10	.043	32	22	.28	163	.009	2	.92	.006	.07	1	<1	3.1	<1	<.01	3
STANDARD C3	25.3	67	34	170	5.0	37	12	810	3.28	55	22	<2	19	28	24.6	14.7	21.3	77	.58	.094	18	177	.61	157	.086	23	1.79	.042	.17	15	1	4.3	<1	.03	8
STANDARD G-2	1.6	2	2	45	<.1	7	1	552	2.01	<1	2	<2	3	70	<.2	<.5	<.5	43	.64	.103	8	79	.60	232	.128	5	.90	.078	.50	2	<1	2.5	<1	<.01	5

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
- SAMPLE TYPE: SOIL SS80 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 17 2000 DATE REPORT MAILED: Oct 26/00 SIGNED BY: .....D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
351533	.8	16	24	50	<.1	18	7	323	2.87	22	1	<2	5	8	<.2	.8	.9	21	.09	.033	27	20	.20	86	.007	2	1.01	.004	.06	1	<1	1.1	<1	<.01	4
351534	.7	10	13	33	.1	11	3	89	1.92	13	<1	<2	4	6	<.2	<.5	<.5	20	.06	.031	24	17	.17	98	.005	3	.97	.004	.06	<1	<1	1.1	<1	.01	4
351535	.9	25	20	73	<.1	38	9	356	3.91	25	1	<2	5	17	<.2	1.3	.6	25	.24	.069	25	30	.33	166	.005	2	1.36	.007	.11	<1	<1	1.6	<1	.01	5
351536	.7	20	21	52	<.1	24	9	338	3.12	28	1	<2	5	9	<.2	.8	.9	25	.10	.044	26	23	.28	136	.007	1	1.01	.004	.08	1	<1	1.5	<1	.01	4
351537	.7	44	22	78	.2	43	18	728	3.39	36	2	<2	8	103	.2	.8	.8	23	2.34	.065	19	25	.59	100	.015	2	1.08	.009	.11	<1	<1	3.2	<1	.05	4
351538	.8	42	31	77	.2	43	19	742	3.43	43	1	<2	9	72	.3	<.5	1.2	19	1.55	.069	24	22	.43	90	.013	2	.88	.007	.09	<1	<1	2.9	<1	.03	3
351539	.8	35	41	62	.1	40	17	645	3.13	44	1	<2	8	33	.2	.9	1.5	16	.56	.068	25	19	.31	70	.012	4	.62	.006	.07	<1	<1	2.5	<1	.03	3
351540	.4	94	5	116	<.1	227	47	419	6.92	<1	4	<2	2	50	<.2	2.1	<.5	134	.48	.201	16	257	2.54	223	.036	<1	2.59	.005	.07	<1	<1	16.4	<1	<.01	13
351541	.5	41	24	77	<.1	34	8	993	3.22	8	2	<2	12	11	<.2	.9	.9	5	.08	.056	27	9	.09	48	.003	<1	.44	.003	.04	<1	<1	1.7	<1	<.01	1
351542	1.2	34	32	67	.1	44	17	883	3.16	34	2	<2	9	14	.2	.8	1.9	13	.16	.058	23	21	.21	69	.010	<1	.50	.004	.04	<1	<1	2.2	<1	.04	3
RE 351542	1.0	32	31	64	.1	40	16	871	3.13	32	2	<2	7	14	.2	1.1	1.3	12	.16	.057	22	15	.21	68	.011	<1	.50	.004	.04	1	<1	2.2	<1	.03	2
351543	1.0	37	25	63	.1	42	17	993	3.15	34	2	<2	8	14	.2	1.0	1.5	17	.14	.060	24	21	.21	71	.018	<1	.52	.004	.03	1	<1	2.7	<1	.01	2
351546	.8	37	33	71	.2	42	18	768	3.28	42	1	<2	10	38	.3	.8	1.5	18	.67	.072	28	19	.40	99	.011	2	.76	.007	.08	<1	<1	2.9	<1	.02	3
351547	.7	40	29	70	.2	42	17	845	3.16	30	1	<2	8	136	.2	1.4	1.1	22	2.28	.061	19	24	.53	122	.011	3	1.02	.008	.12	<1	<1	3.0	<1	.04	4
351548	1.0	31	30	56	.2	34	15	682	2.69	35	1	<2	6	14	.3	1.4	1.2	18	.17	.057	26	18	.23	122	.008	3	.70	.004	.07	1	<1	2.1	<1	<.01	3
351549	1.3	23	21	68	.6	27	15	870	3.41	21	1	<2	3	17	.3	<.5	<.5	21	.26	.054	21	17	.23	172	.006	2	.87	.004	.07	<1	<1	1.9	<1	.02	1
351550	1.2	15	14	42	.5	15	5	476	2.26	18	1	<2	2	7	<.2	<.5	<.5	18	.11	.035	22	14	.18	116	.007	2	.59	.003	.05	<1	<1	1.0	<1	.01	2
351551	1.1	23	22	96	<.1	29	12	803	4.24	21	1	<2	7	3	.2	.9	.9	23	.03	.054	28	22	.24	72	.009	<1	1.08	.004	.05	1	<1	1.6	<1	.01	2
351552	1.1	18	65	76	.4	28	12	889	3.56	21	1	<2	5	10	<.2	<.5	1.1	23	.15	.056	28	19	.27	103	.008	1	.94	.004	.06	1	<1	1.6	<1	.01	2
351553	2.8	68	616	117	1.6	83	24	1182	6.57	34	3	<2	11	24	.5	1.4	5.3	35	.30	.068	21	37	.32	357	.007	<1	2.22	.009	.20	<1	<1	5.7	<1	.02	3
351554	1.2	28	128	67	.6	32	16	946	3.65	22	1	<2	5	16	<.2	<.5	1.6	27	.25	.057	23	22	.25	163	.007	<1	1.16	.006	.09	<1	<1	2.3	<1	.02	4
351555	1.3	31	29	55	.1	29	12	974	3.29	32	1	<2	6	9	<.2	<.5	1.2	17	.14	.042	28	14	.22	74	.003	<1	.78	.003	.06	1	<1	1.7	<1	<.01	2
351556	.8	23	30	54	.3	28	13	834	3.41	24	1	<2	5	11	<.2	<.5	.9	18	.17	.037	28	17	.28	74	.004	1	.89	.004	.05	1	<1	2.0	<1	.01	2
351557	.6	21	28	54	.3	24	12	671	3.04	24	1	<2	3	12	<.2	<.5	.7	22	.19	.052	26	16	.23	93	.005	<1	.89	.004	.07	1	<1	2.0	<1	.01	3
STANDARD C3	26.9	67	35	175	5.5	37	12	640	3.38	57	23	<2	21	28	24.0	15.1	23.0	85	.61	.094	19	175	.65	158	.089	22	1.82	.046	.18	15	1	4.5	<1	.03	7
STANDARD G-2	1.6	2	3	41	<.1	7	4	499	1.78	1	2	<2	5	70	<.2	<.5	<.5	37	.59	.099	8	76	.55	220	.120	1	.82	.079	.47	2	<1	2.2	<1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004088R Page 1

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: K. Ross

SAMPLE#	Au* ppb
351390	81.5
351391	32.5
351392	63.9
351393	49.9
351394	123.3
351395	40.5
351396	21.0
351397	123.5
351398	20.6
351399	70.6
351400	131.0
351401	62.1
351403	88.9
351404	16.0
351405	26.4
RE 351405	42.7
351406	29.5
351407	247.2
351408	61.3
351409	42.5
351410	170.5
351411	80.2
351412	318.6
351413	267.3
351414	18.5
351415	179.0
351416	86.4
351417	166.3
351419	61.3
351420	33.3
351421	96.2
351422	20.1
351423	202.2
351424	40.7
STANDARD DS2	194.7

AU* BY ACID LEACHED, ANALYSIS BY ICP/MS. (10 gm)
- SAMPLE TYPE: SOIL PULP
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: NOV 23 2000 DATE REPORT MAILED: Nov 27/00 SIGNED BY. C. ... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au* ppb
351462	22.6
351463	13.8
351464	40.8
351465	7.5
351466	8.1
351468	91.5
351469	171.9
351470	23.2
351471	67.4
351472	10.7
351473	42.6
351474	37.3
351475	70.0
RE 351475	30.7
351476	72.6
351477	61.8
351478	73.8
351479	32.8
351481	9.1
351482	32.8
351483	72.8
351484	7.3
351485	19.2
351486	51.4
351487	22.5
351488	15.8
351489	52.6
351490	121.3
351491	62.3
351492	43.8
351493	48.3
351494	22.3
351495	40.4
351496	34.6
STANDARD DS2	195.8

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data /FA

SAMPLE#	Au* ppb
351497	50.4
351498	10.2
351499	51.5
351501	35.6
351502	26.3
351503	30.6
351504	38.7
351505	233.6
351506	52.9
351507	53.1
351508	45.4
351509	32.0
351510	80.2
RE 351510	25.6
351511	70.0
351512	35.9
351513	29.5
351514	11.1
351515	14.9
351516	25.4
351517	24.9
351518	32.4
351519	21.6
351520	28.2
351521	13.7
351522	13.1
351523	13.9
351524	25.6
351525	28.1
351528	84.5
351529	78.0
351530	244.9
351531	103.7
351532	251.5
STANDARD DS2	191.0

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data __ FA ___

SAMPLE#	Au* ppb
351533	22.2
351534	32.5
351535	27.0
351536	27.5
351537	16.9
351538	84.6
351539	156.5
351540	1.1
351541	3.0
351542	44.3
RE 351542	86.5
351543	454.1
351546	76.3
351547	31.0
351548	23.7
351549	33.0
351550	34.3
351551	105.5
351552	15.8
351553	31.3
351554	18.2
351555	53.4
351556	23.8
351557	31.1
STANDARD DS2	195.2

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004150 Page 1

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
351559	.9	43	42	68	.3	42	19	938	3.80	43	2	<2	11	33	<.2	.6	<.5	15	.53	.074	38	17	.31	97	.013	5	.76	.006	.09	2	<1	3.1	<1	.02	2
351560	1.0	47	46	74	.3	44	20	888	3.96	50	2	<2	9	50	<.2	.5	.6	19	.99	.067	26	19	.34	84	.013	5	.84	.005	.11	2	<1	3.2	<1	.06	2
351597	.8	47	39	87	.3	54	22	1252	4.55	37	2	<2	9	24	<.2	1.0	.5	20	.37	.074	29	26	.39	84	.009	4	.96	.005	.10	2	<1	3.5	<1	.04	2
351602	.6	37	34	68	.2	37	17	882	3.26	29	1	<2	8	24	<.2	<.5	.7	20	.42	.078	31	16	.35	76	.023	3	.71	.002	.05	2	<1	2.9	<1	<.01	2
351603	.8	49	40	87	.3	46	21	921	4.09	33	2	<2	10	36	<.2	.6	.6	26	.66	.066	34	24	.47	118	.017	4	1.14	.006	.11	2	<1	3.9	<1	.01	3
351604	1.0	49	41	89	.3	47	22	875	4.24	41	2	<2	11	36	<.2	.6	.8	24	.65	.066	35	24	.43	147	.015	2	1.16	.006	.13	2	<1	4.0	<1	<.01	3
351605	.9	32	33	69	.8	31	6	113	1.49	9	2	<2	3	13	.2	<.5	<.5	20	.12	.047	32	19	.24	244	.005	<1	1.13	<.001	.08	1	<1	2.8	<1	.02	3
351606	.6	25	23	73	.4	27	11	370	3.03	20	2	<2	4	15	<.2	.9	<.5	26	.18	.061	29	27	.31	182	.007	<1	1.30	.001	.10	2	<1	2.7	<1	.01	3
351607	.5	20	18	61	.3	24	10	513	2.55	12	1	<2	3	13	<.2	<.5	<.5	27	.14	.055	29	24	.34	186	.011	<1	1.22	.001	.10	1	<1	2.4	<1	<.01	3
351608	.7	40	33	74	.3	41	17	778	3.71	36	1	<2	8	16	<.2	1.0	<.5	27	.14	.048	36	24	.36	166	.015	1	1.17	.003	.14	2	<1	3.8	<1	<.01	3
351609	1.5	32	19	50	.3	28	10	369	2.45	19	2	<2	5	10	<.2	1.0	<.5	22	.08	.030	31	18	.25	148	.019	1	.85	<.001	.07	1	<1	3.3	<1	<.01	2
351611	1.1	16	18	39	.1	13	4	342	3.37	17	1	<2	2	5	<.2	.7	<.5	27	.05	.157	24	20	.15	73	.012	1	.79	<.001	.05	1	<1	1.0	<1	.01	3
351612	2.1	46	37	129	2.4	49	40	1858	7.29	41	3	<2	4	21	<.2	2.3	<.5	32	.28	.067	26	32	.31	240	.014	<1	1.38	<.001	.08	2	<1	4.0	<1	.02	2
351613	2.3	50	25	88	1.2	39	17	487	3.35	25	3	<2	4	12	<.2	1.5	<.5	32	.06	.047	30	29	.31	240	.009	<1	1.55	<.001	.11	2	<1	3.6	<1	.01	3
351614	1.6	35	32	89	2.5	36	9	136	3.02	32	2	<2	3	11	<.2	.6	<.5	27	.10	.058	28	26	.29	196	.008	2	1.22	<.001	.08	2	<1	3.1	<1	.02	3
RE 351614	1.7	37	32	92	2.5	37	9	140	3.07	33	3	<2	3	11	<.2	.7	<.5	29	.10	.059	28	28	.30	204	.008	3	1.25	<.001	.08	2	<1	3.1	<1	.02	3
351615	.5	29	27	55	.7	28	9	110	1.65	10	2	<2	6	14	<.2	.5	<.5	19	.19	.056	35	24	.31	152	.010	<1	.84	<.001	.05	1	<1	3.1	<1	.01	2
351616	.9	29	29	118	2.7	47	15	303	3.08	21	4	<2	4	22	.4	<.5	<.5	28	.22	.067	36	33	.35	236	.008	<1	1.37	<.001	.07	2	<1	4.7	<1	.02	3
351617	.9	29	35	74	1.0	35	14	539	3.37	36	3	<2	4	22	.2	<.5	<.5	29	.26	.065	31	26	.29	227	.007	1	1.22	<.001	.07	2	<1	3.4	<1	.02	3
351618	.8	36	40	77	.4	41	18	756	3.71	46	2	<2	8	23	.2	<.5	.6	17	.38	.065	28	20	.33	97	.010	1	.81	<.001	.07	1	<1	3.3	<1	.05	2
351624	1.3	42	29	68	.4	38	16	627	3.33	27	2	<2	9	14	<.2	1.2	<.5	14	.16	.048	31	14	.17	67	.009	<1	.48	<.001	.03	2	<1	2.3	<1	.03	1
351628	.6	52	33	93	.2	47	21	898	4.17	32	2	<2	9	63	<.2	.6	.5	29	1.43	.072	26	28	.64	100	.019	<1	1.25	.005	.11	1	<1	4.1	<1	.03	3
351629	.4	97	9	49	.1	57	20	1075	3.25	14	3	<2	8	35	<.2	.6	<.5	2	1.15	.060	12	8	.20	38	.002	2	.16	<.001	.03	1	<1	1.9	<1	.11	<1
351630	.9	46	57	118	.3	72	21	835	4.60	28	3	<2	9	23	<.2	1.0	.7	13	.35	.087	21	14	.23	83	.009	<1	.62	<.001	.06	2	<1	3.2	<1	.10	1
351631	.7	44	39	87	.3	46	19	768	3.81	29	2	<2	8	34	<.2	1.1	.5	26	.59	.060	36	26	.45	144	.018	3	1.20	.003	.09	1	<1	4.0	<1	<.01	3
351632	1.3	26	19	55	.2	24	8	231	2.86	23	1	<2	3	8	<.2	.7	<.5	27	.03	.030	27	23	.27	150	.010	<1	1.05	<.001	.09	2	<1	1.8	<1	<.01	3
351633	1.2	10	13	28	.6	9	2	95	2.40	12	1	<2	3	7	<.2	<.5	<.5	23	.04	.047	25	17	.14	107	.016	<1	.77	<.001	.05	1	<1	1.0	<1	<.01	3
351634	2.9	23	18	52	2.9	21	5	161	3.75	16	1	<2	3	10	.2	1.0	<.5	32	.09	.059	23	26	.21	166	.018	1	1.16	<.001	.05	2	<1	1.6	<1	.02	2
351636	.9	48	59	81	.4	48	23	1000	4.30	51	2	<2	9	52	<.2	.5	.5	21	.92	.073	26	21	.45	82	.014	2	.92	.002	.08	2	<1	3.4	<1	.06	2
351638	1.3	45	34	74	.3	46	20	953	4.15	45	1	<2	10	23	<.2	.7	2.0	20	.29	.071	41	21	.33	99	.012	2	1.01	.002	.12	2	<1	3.4	<1	<.01	2
351639	.5	40	36	78	.3	43	19	847	3.94	47	1	<2	11	25	<.2	.7	2.2	19	.35	.065	34	20	.36	87	.016	1	.98	.003	.09	2	<1	3.2	<1	<.01	2
351640	.5	36	31	71	.2	37	16	690	3.57	42	1	<2	8	17	<.2	.6	1.4	17	.23	.062	35	17	.30	92	.012	1	.82	<.001	.06	2	<1	2.7	<1	.01	2
351641	.7	43	30	78	.2	47	20	822	3.95	35	2	<2	9	24	<.2	.9	.7	22	.36	.061	32	26	.37	89	.013	3	.98	.001	.08	2	<1	3.8	<1	<.01	2
351642	.6	38	20	70	.2	39	14	631	3.78	32	2	<2	9	12	<.2	1.1	.6	17	.10	.058	32	20	.23	55	.016	1	.65	<.001	.05	3	<1	2.9	<1	<.01	2
STANDARD C3	27.7	66	35	168	5.3	37	12	787	3.36	60	24	2	19	30	22.2	18.3	23.4	81	.59	.095	21	179	.62	162	.090	23	1.86	.037	.16	15	1	4.6	<1	.02	7
STANDARD G-2	1.7	3	3	44	.1	7	4	552	2.03	<1	3	<2	4	83	<.2	<.5	<.5	42	.69	.104	10	83	.62	253	.142	1	1.06	.117	.53	3	<1	2.7	1	<.01	4

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
- SAMPLE TYPE: SOIL SS80 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 19 2000 DATE REPORT MAILED: Oct 28/00 SIGNED BY: C. Toye D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
351644	1.6	47	294	20	3.8	32	11	631	1.77	118	1	<2	6	22	.4	<.5	24.2	1	.41	.023	6	4	.11	31	.001	8	.11	.001	.05	1	<1	1.0	<1	.66	<1
351645	.5	50	26	69	.4	40	22	692	3.08	37	2	<2	12	26	<.2	.9	.7	11	.30	.062	30	11	.27	83	.006	2	.49	.001	.05	1	<1	2.2	<1	.06	1
351646	.3	33	19	62	.1	31	17	431	2.38	40	2	<2	18	35	<.2	.5	.7	7	.71	.067	26	8	.19	57	.003	3	.37	.001	.06	1	<1	2.1	<1	.13	1
351647	.3	51	18	57	<.1	41	19	527	2.83	27	3	<2	15	37	<.2	.7	.5	7	1.25	.057	21	8	.19	70	.005	4	.40	.002	.09	1	<1	2.4	<1	.16	1
351648	.4	43	36	88	.1	44	19	758	3.97	37	2	<2	11	31	<.2	.8	.6	23	.50	.069	37	22	.39	111	.014	4	1.15	.009	.13	1	<1	3.7	<1	<.01	2
351649	.6	26	25	56	.1	26	10	366	2.91	30	1	<2	4	9	<.2	.5	.5	18	.10	.042	29	17	.20	114	.006	1	.98	.003	.08	2	<1	1.9	<1	<.01	2
351650	1.0	16	18	34	.2	12	2	90	2.34	13	1	<2	4	7	<.2	.5	<.5	30	.05	.046	23	18	.15	102	.010	1	1.03	.002	.07	1	<1	1.4	<1	<.01	3
351651	.9	22	20	50	.1	20	7	249	3.19	22	1	<2	5	6	<.2	.6	<.5	31	.05	.040	25	23	.24	97	.012	1	1.14	.002	.08	2	<1	1.8	<1	<.01	3
351652	3.3	28	17	52	.7	24	5	161	3.33	16	1	<2	3	11	<.2	2.0	<.5	39	.06	.041	17	33	.21	194	.026	1	1.50	.003	.09	1	<1	2.2	<1	.02	2
351653	2.3	12	12	33	.1	11	3	193	2.92	13	1	<2	2	6	<.2	<.5	<.5	40	.03	.045	23	18	.12	99	.026	3	.67	.001	.04	1	<1	1.0	<1	<.01	3
351654	.4	14	12	42	<.1	18	6	185	2.22	19	1	<2	6	9	<.2	<.5	.6	20	.11	.048	36	18	.30	70	.015	1	.86	.004	.08	1	<1	1.8	<1	<.01	2
351655	.5	43	28	79	.1	49	24	984	4.03	35	2	<2	10	25	<.2	.9	1.0	25	.30	.068	34	23	.36	80	.015	3	1.08	.005	.08	2	<1	3.8	<1	<.01	2
351656	.6	32	22	70	.1	35	14	590	3.59	38	1	<2	7	22	.2	.8	1.4	22	.28	.064	36	20	.33	99	.010	1	1.02	.003	.09	2	<1	2.7	<1	.01	2
351657	.7	42	30	73	.2	45	20	940	4.12	48	2	<2	11	51	<.2	<.5	1.5	21	.83	.060	35	21	.34	99	.013	3	1.05	.008	.13	1	<1	3.6	<1	<.01	2
351659	.8	43	31	83	.2	37	15	326	3.87	26	2	<2	13	21	<.2	.8	.5	21	.27	.068	39	19	.29	93	.016	2	.87	.002	.06	2	<1	3.8	<1	.01	2
351660	1.0	39	32	77	.3	36	14	159	2.51	22	2	<2	7	18	.2	1.0	.7	25	.25	.068	30	20	.32	91	.017	<1	.91	.003	.06	2	<1	3.1	<1	.03	2
351661	.9	32	24	69	.1	35	14	658	3.27	24	2	<2	8	17	<.2	.8	.6	22	.19	.058	29	17	.28	89	.020	2	.78	.002	.05	2	<1	3.0	<1	.01	1
RE 351661	.8	34	24	71	.1	36	15	684	3.41	25	2	<2	9	18	<.2	.9	.5	22	.20	.059	28	18	.29	89	.020	<1	.81	.003	.05	1	<1	3.2	<1	.01	2
351663	.6	39	29	75	.3	40	18	751	3.70	37	1	<2	8	28	<.2	<.5	.7	23	.43	.066	33	21	.35	102	.014	<1	.99	.004	.09	1	<1	3.2	<1	.01	2
351664	1.8	51	27	101	.2	55	22	817	4.06	22	4	<2	8	24	<.2	1.3	.5	46	.28	.055	23	31	.46	147	.042	3	1.60	.005	.08	2	<1	5.6	<1	.01	4
351665	.7	44	33	80	.2	43	20	932	4.04	58	2	<2	11	31	<.2	.7	.9	18	.59	.065	28	17	.30	82	.009	3	.83	.005	.09	2	<1	3.2	<1	.01	2
351666	1.2	25	19	57	.3	24	8	211	3.41	29	1	<2	7	5	<.2	.5	.5	25	.03	.045	29	23	.24	124	.010	1	1.14	.001	.08	2	<1	2.0	<1	<.01	3
351667	2.1	30	17	68	1.0	22	7	450	3.02	13	1	<2	2	7	<.2	.8	<.5	30	.03	.052	21	28	.33	238	.010	1	1.29	<.001	.09	1	<1	1.7	<1	.01	3
351668	2.6	26	17	61	.7	21	5	291	3.62	16	1	<2	1	7	<.2	1.1	<.5	33	.03	.074	20	29	.27	269	.010	3	1.13	.001	.11	2	<1	1.4	<1	.02	3
351669	1.3	28	24	71	.1	29	9	280	3.42	25	2	<2	4	6	<.2	.6	<.5	26	.05	.043	27	26	.30	132	.013	1	1.10	.002	.09	1	<1	1.8	<1	<.01	2
351670	2.3	36	23	71	1.7	30	7	381	2.45	14	3	<2	1	27	.3	1.0	<.5	26	.23	.066	19	22	.21	204	.006	1	.85	.001	.06	1	<1	1.8	<1	.02	2
351671	1.9	61	40	70	5.3	38	6	213	1.99	11	7	<2	1	55	.5	.9	.6	28	.48	.118	24	26	.29	311	.006	1	1.36	.003	.10	1	<1	2.8	<1	.07	3
351672	2.5	35	34	95	1.0	35	11	457	3.07	16	2	<2	2	20	.3	.8	<.5	32	.12	.081	19	27	.25	306	.007	1	1.12	.001	.08	1	<1	2.0	<1	.02	3
351673	2.2	30	25	88	.7	37	10	457	2.77	16	2	<2	2	20	<.2	.9	<.5	27	.13	.059	21	23	.26	202	.007	<1	.92	<.001	.06	1	<1	2.0	<1	.01	2
351674	1.3	43	39	83	1.1	49	19	908	3.95	40	2	4	6	20	.2	.7	1.1	22	.23	.069	28	23	.34	128	.009	<1	.95	.005	.07	2	<1	3.1	<1	.02	2
351676	.8	36	28	70	.2	34	13	305	2.77	23	2	<2	8	20	<.2	.7	.6	22	.30	.072	33	20	.31	78	.018	1	.73	.002	.04	2	<1	2.7	<1	.02	2
351677	.9	39	36	81	.2	41	17	672	3.63	25	2	<2	8	18	<.2	.5	.8	19	.25	.061	30	22	.27	103	.009	<1	.78	.002	.06	2	<1	3.0	<1	.02	2
351679	.9	42	29	73	.2	43	20	781	3.95	43	2	<2	8	32	<.2	1.0	1.3	25	.38	.064	29	21	.28	97	.017	2	1.00	.006	.07	2	<1	3.8	<1	.01	2
351680	.9	39	30	68	.2	42	18	615	3.76	48	1	<2	9	36	<.2	<.5	2.2	19	.55	.064	35	18	.29	92	.010	1	.92	.005	.11	1	<1	3.2	<1	.01	2
STANDARD C3	27.6	66	35	165	5.4	37	12	801	3.40	60	24	2	20	30	23.1	17.9	23.4	83	.61	.097	20	184	.63	166	.089	26	1.87	.046	.18	16	1	4.8	<1	.03	7
STANDARD G-2	1.7	3	4	44	<.1	8	4	565	2.09	<1	3	<2	4	97	<.2	<.5	<.5	43	.74	.104	10	85	.63	271	.133	2	1.21	.173	.59	3	<1	3.0	<1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
351770	.4	19	14	55	.1	18	8	277	3.14	36	1	<2	4	8	<.2	.8	<.5	22	.08	.041	31	18	.20	61	.007	<1	.96	.002	.05	2	<1	1.4	<1	<.01	3
351771	.5	24	24	54	.3	22	9	260	3.67	71	1	<2	6	8	<.2	1.1	1.2	14	.04	.051	32	13	.17	47	.003	<1	.71	<.001	.04	2	<1	1.3	1	.01	2
351773	.8	30	40	56	1.0	25	12	514	3.76	73	2	<2	2	31	<.2	1.1	.9	36	.26	.101	18	22	.21	114	.007	<1	1.31	.003	.11	2	<1	2.2	<1	.03	4
351775	.3	27	21	62	.1	34	16	538	3.61	43	2	<2	6	15	<.2	.7	<.5	24	.22	.072	32	24	.42	61	.012	<1	1.21	.004	.08	1	<1	2.5	<1	<.01	3
351776	.5	32	21	68	.2	34	16	620	3.68	33	2	<2	5	18	.2	.8	<.5	24	.21	.077	29	25	.38	71	.005	<1	1.21	.001	.07	2	<1	2.6	<1	<.01	3
351777	.4	25	20	79	.2	29	16	415	4.14	35	2	<2	4	19	<.2	<.5	<.5	24	.21	.100	27	22	.35	69	.006	<1	1.18	.001	.07	2	<1	1.9	<1	.01	3
351778	.4	42	20	80	.3	40	19	864	3.91	36	2	<2	5	21	.2	.7	<.5	24	.26	.090	26	21	.39	78	.005	<1	1.29	.001	.08	2	<1	3.2	<1	.01	3
351779	.6	30	13	92	.8	30	14	461	3.92	30	2	<2	2	22	<.2	.7	<.5	18	.31	.122	22	16	.13	85	.005	<1	1.02	.002	.07	2	<1	2.2	<1	.02	3
351780	1.2	49	16	98	.4	32	12	267	4.24	40	2	<2	2	24	.3	1.8	.5	23	.32	.119	26	13	.10	77	.006	<1	.68	<.001	.05	2	<1	1.5	<1	.02	3
351782	1.2	29	26	71	.3	27	14	663	3.70	36	2	<2	3	16	.2	1.2	<.5	25	.19	.058	27	20	.21	75	.007	<1	.99	<.001	.07	2	<1	1.9	1	.02	3
351783	1.2	25	16	56	.5	25	9	475	3.02	29	1	<2	4	13	<.2	.6	.5	20	.10	.063	27	20	.26	98	.004	<1	1.19	.001	.08	2	<1	2.2	1	.01	3
351784	.8	29	27	71	.2	28	16	617	3.78	38	2	<2	4	16	<.2	.6	<.5	24	.20	.069	29	21	.31	75	.007	<1	1.16	.001	.07	2	<1	2.2	<1	.01	3
351786	2.6	29	21	67	<.1	25	9	280	3.54	38	1	<2	6	6	<.2	.7	.5	17	.03	.054	29	19	.20	57	.005	<1	1.11	<.001	.06	2	<1	1.5	1	.01	2
351787	.3	21	19	49	.2	14	7	242	2.67	23	<1	<2	5	4	<.2	.5	<.5	16	.03	.066	28	14	.18	46	.004	<1	.96	<.001	.04	2	<1	1.1	<1	.01	2
351789	.6	26	22	53	.2	22	9	352	3.21	31	1	<2	4	8	<.2	<.5	.6	21	.06	.042	29	20	.23	98	.005	<1	1.02	<.001	.07	2	<1	1.7	<1	<.01	3
351790	.4	34	26	73	.3	28	16	714	3.78	41	1	<2	3	14	<.2	<.5	<.5	26	.17	.063	30	20	.22	112	.005	<1	1.10	<.001	.08	2	<1	2.1	1	.01	3
351791	.2	28	20	85	.2	29	15	697	3.51	33	1	<2	4	16	.2	.7	<.5	21	.19	.069	32	18	.28	93	.005	<1	1.12	.001	.08	2	<1	2.4	<1	<.01	3
351792	.4	35	23	81	.3	32	19	763	3.48	42	2	<2	4	16	.3	<.5	.5	19	.18	.075	30	18	.29	69	.007	<1	1.11	<.001	.08	2	<1	2.5	<1	.01	3
RE 351792	.4	36	24	84	.3	33	20	790	3.60	45	2	<2	4	16	.2	<.5	.5	19	.19	.078	31	18	.30	71	.006	<1	1.15	<.001	.09	2	<1	2.5	<1	.01	3
351793	.7	24	23	89	.1	22	8	240	4.11	29	1	<2	2	14	.2	.7	<.5	29	.15	.126	22	20	.18	107	.010	<1	1.01	<.001	.06	2	<1	1.4	1	.02	3
351794	1.7	33	26	89	<.1	35	12	319	4.24	43	1	<2	7	7	<.2	1.1	.5	20	.05	.078	32	21	.30	78	.006	<1	1.15	<.001	.06	2	<1	1.9	1	<.01	2
351795	.7	26	22	71	.2	25	10	280	4.10	102	1	<2	3	11	.2	1.0	1.1	20	.09	.101	26	17	.22	68	.005	<1	.95	<.001	.06	2	<1	1.4	<1	.01	2
351798	1.1	55	37	91	1.0	42	20	1117	4.90	134	4	<2	2	35	.3	2.0	2.7	29	.30	.136	26	23	.23	105	.006	<1	1.38	.001	.11	2	<1	3.4	<1	.03	3
351799	.6	27	23	79	.5	27	15	1019	3.95	48	2	<2	2	24	<.2	.6	.8	33	.18	.093	28	23	.27	76	.010	<1	1.12	.001	.08	2	<1	2.0	<1	.02	3
351800	.4	21	21	60	1.1	25	9	231	4.69	46	1	<2	7	7	<.2	1.1	<.5	26	.06	.162	28	28	.30	49	.005	<1	1.44	<.001	.04	2	<1	1.8	1	.01	3
351801	.3	25	15	56	.1	24	9	224	4.21	50	<1	<2	7	5	<.2	1.0	1.1	15	.02	.078	33	15	.16	34	.004	<1	.80	<.001	.04	2	<1	1.3	1	<.01	2
351802	.4	26	17	63	.1	28	10	400	4.28	51	1	<2	4	6	<.2	1.3	.7	18	.05	.083	27	20	.21	52	.005	<1	1.10	<.001	.06	2	<1	1.4	<1	.02	2
351803	.3	18	12	55	.3	19	7	182	3.53	30	<1	<2	6	6	<.2	.6	<.5	19	.04	.058	29	18	.23	54	.005	<1	1.14	<.001	.05	2	<1	1.3	<1	<.01	3
351804	.2	21	16	52	.1	21	9	269	4.03	37	1	<2	5	5	<.2	.6	<.5	22	.05	.051	31	21	.32	59	.007	<1	1.05	<.001	.06	2	<1	1.5	<1	<.01	3
351805	.2	29	16	61	.5	34	11	285	3.82	36	1	<2	5	7	<.2	.5	<.5	26	.08	.070	30	27	.39	76	.009	<1	1.46	<.001	.07	2	<1	2.1	1	.01	3
351806	.2	33	28	69	.1	41	14	443	4.15	37	1	<2	6	8	<.2	1.0	<.5	33	.09	.058	35	36	.47	126	.015	<1	1.67	.002	.13	2	<1	3.1	1	<.01	4
351807	.5	29	16	65	<.1	31	8	266	2.90	26	1	<2	10	8	<.2	.5	.8	17	.04	.035	47	21	.36	79	.012	<1	1.02	<.001	.06	1	<1	2.2	<1	<.01	3
351809	.6	30	18	60	.2	28	8	313	3.69	40	1	<2	3	9	<.2	.8	<.5	21	.09	.060	26	22	.23	84	.012	<1	1.09	.001	.08	2	<1	1.9	<1	.01	2
351810	.6	24	20	62	.3	26	9	151	2.54	24	1	<2	4	12	<.2	.7	<.5	21	.12	.069	35	22	.30	129	.009	<1	1.11	<.001	.07	1	<1	2.6	<1	<.01	3
STANDARD C3	26.2	66	34	165	5.4	36	11	776	3.28	57	23	3	20	29	21.3	17.6	22.2	81	.59	.091	21	177	.61	158	.093	23	1.86	.037	.16	15	1	4.6	1	.02	7
STANDARD G-2	1.4	3	3	44	<.1	7	4	535	2.00	<1	3	<2	4	77	<.2	<.5	<.5	40	.66	.101	10	79	.61	235	.136	3	.97	.093	.49	3	<1	2.7	1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
351811	1.5	49	25	86	.2	45	19	804	4.20	44	2	<2	7	23	<.2	2.7	1.2	27	.18	.081	25	23	.27	115	.020	1	.93	.004	.05	2	<1	4.2	<1	.01	2
351813	.5	35	18	82	.3	45	16	472	3.74	9	2	<2	5	40	<.2	.9	<.5	58	.44	.090	17	38	.54	176	.157	<1	1.48	.014	.07	1	<1	6.2	<1	<.01	4
351814	.7	44	28	82	.2	43	19	985	3.80	30	2	<2	9	19	<.2	1.2	1.0	20	.20	.057	25	17	.24	88	.028	1	.78	.005	.07	2	<1	3.3	1	<.01	2
351815	1.8	51	50	109	.3	60	23	1420	4.50	25	2	<2	7	29	<.2	.7	<.5	39	.32	.090	20	29	.49	194	.047	2	1.41	.006	.07	1	<1	4.5	<1	<.01	3
351816	1.3	43	42	94	.3	36	15	637	3.15	25	2	<2	3	12	.3	.8	.6	24	.11	.052	24	24	.31	178	.011	<1	1.22	<.001	.08	2	<1	3.5	<1	<.01	3
351817	1.6	30	31	66	.6	24	11	440	3.07	23	2	<2	2	16	<.2	<.5	.5	24	.16	.061	22	21	.27	183	.008	<1	1.08	<.001	.07	1	<1	1.9	<1	.02	2
RE 351817	1.4	31	32	68	.6	25	12	448	3.14	23	2	<2	2	17	<.2	.9	<.5	23	.17	.061	22	21	.27	186	.007	<1	1.10	<.001	.07	2	<1	1.9	<1	.01	2
351818	1.5	40	34	67	.2	41	18	846	3.99	69	2	<2	9	15	<.2	1.3	2.5	17	.16	.048	33	17	.25	112	.008	<1	.92	.001	.12	3	<1	2.8	<1	<.01	2
351820	.9	39	39	70	.2	41	18	873	3.87	70	2	<2	11	46	<.2	.6	3.1	17	.73	.059	29	18	.33	82	.011	2	.96	.002	.11	3	<1	3.3	<1	<.01	2
351822	2.1	36	28	83	.7	29	5	212	1.90	14	2	<2	1	19	.3	1.6	<.5	18	.20	.048	16	12	.12	132	.008	<1	.46	<.001	.03	1	<1	1.2	<1	.01	1
STANDARD C3	27.0	67	34	168	5.3	36	11	784	3.34	59	23	2	20	29	22.0	18.2	23.1	80	.59	.095	19	178	.61	161	.095	22	1.85	.038	.16	16	1	4.7	1	.02	7
STANDARD G-2	1.6	2	3	44	<.1	7	4	538	2.01	<1	3	<2	4	78	<.2	<.5	<.5	40	.66	.104	9	79	.61	246	.137	<1	.99	.105	.51	2	<1	2.7	<1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004150R Page 1

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: K. Ross

SAMPLE#	Au* ppb
351559	105.6
351560	689.9
351597	86.1
351602	37.6
351603	54.8
351604	73.1
351605	63.7
351606	17.6
351607	6.5
351608	615.8
351609	13.6
351611	21.9
351612	74.8
351613	11.7
351614	29.9
RE 351614	56.7
351615	161.9
351616	62.1
351617	59.7
351618	333.0
351624	416.3
351628	28.9
351629	38.2
351630	41.2
351631	72.2
351632	15.6
351633	5.8
351634	7.1
351636	80.0
351638	78.1
351639	142.6
351640	290.0
351641	50.7
351642	101.0
STANDARD DS2	190.6

AU* BY ACID LEACHED, ANALYSIS BY ICP/MS. (10 gm)
- SAMPLE TYPE: SOIL PULP
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: NOV 23 2000 DATE REPORT MAILED: Nov 27/00 SIGNED BY. D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data FA

SAMPLE#	Au* ppb
351644	2660.1
351645	38.9
351646	61.3
351647	39.8
351648	77.3
351649	59.7
351650	279.2
351651	18.3
351652	8.2
351653	1.8
351654	94.7
351655	106.6
351656	214.3
351657	241.5
351659	126.9
351660	36.0
351661	60.6
RE 351661	31.3
351663	76.2
351664	87.3
351665	117.1
351666	32.8
351667	6.2
351668	2.8
351669	13.3
351670	106.4
351671	10.2
351672	6.8
351673	52.2
351674	320.4
351676	110.6
351677	251.7
351679	351.1
351680	134.8
STANDARD DS2	216.9

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Au* ppb
351681	3.2
351682	12.7
351683	22.3
351684	121.1
351685	135.6
351686	43.9
351687	49.0
351688	406.6
351691	60.4
351692	40.9
351694	48.1
351695	89.5
351696	83.0
RE 351696	46.6
351697	12.3
351699	55.3
351700	82.5
351751	243.2
351752	478.2
351753	600.1
351754	220.7
351755	174.3
351757	3.8
351758	11.2
351759	61.0
351760	38.3
351761	32.2
351763	31.0
351764	14.2
351765	123.7
351766	43.9
351767	54.7
351768	26.9
351769	35.5
STANDARD DS2	195.0

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Au* ppb
351770	57.1
351771	352.9
351773	188.1
351775	110.6
351776	30.2
351777	40.4
351778	67.0
351779	13.3
351780	16.0
351782	14.2
351783	36.7
351784	92.0
351786	122.5
351787	24.7
351789	361.5
351790	265.8
351791	95.3
351792	21.1
RE 351792	38.8
351793	33.1
351794	81.7
351795	703.8
351798	152.5
351799	41.7
351800	48.1
351801	172.1
351802	74.6
351803	56.1
351804	132.2
351805	40.6
351806	350.3
351807	70.5
351809	106.4
351810	56.7
STANDARD DS2	199.8

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data /-FA

SAMPLE#	Au* ppb
351811	114.5
351813	91.4
351814	78.1
351815	15.0
351816	46.0
351817	44.4
RE 351817	18.5
351818	138.9
351820	95.7
351822	24.5

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004307 Page 1

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
351823	1.6	40	23	82	.8	30	12	788	3.08	20	2	<2	2	17	.2	.9	.5	37	.19	.076	24	29	.33	284	.015	<1	1.27	.005	.11	1	<1	2.8	<1	.02	4
351824	1.5	70	18	127	.8	76	25	433	3.53	10	4	<2	7	22	.2	.9	<.5	59	.25	.068	21	38	.67	491	.060	<1	1.79	.013	.11	1	<1	6.3	<1	<.01	4
351825	1.1	56	19	108	.5	57	21	491	3.35	12	3	<2	7	22	.2	.9	<.5	58	.29	.072	22	33	.59	319	.067	<1	1.51	.010	.08	1	<1	5.8	<1	<.01	4
351828	.7	42	34	86	.3	42	16	720	3.53	21	2	<2	10	14	<.2	1.0	.6	25	.15	.059	26	18	.28	100	.025	<1	.84	.005	.07	1	<1	3.5	<1	<.01	2
351829	.8	40	34	77	.2	41	17	802	3.53	38	2	<2	9	16	.2	.8	1.6	20	.20	.060	32	19	.29	95	.022	<1	.86	.005	.09	1	<1	3.4	<1	<.01	2
351832	.5	42	20	75	.2	40	16	388	3.55	34	1	<2	10	19	<.2	1.3	.7	28	.24	.073	34	19	.29	87	.025	<1	.86	.004	.08	1	<1	3.4	<1	.01	3
351833	.8	60	19	101	.3	52	24	860	4.59	32	2	<2	8	28	<.2	2.2	.6	35	.23	.092	21	22	.22	114	.049	<1	1.08	.009	.09	1	<1	5.2	1	<.01	3
351834	.8	54	27	84	.4	50	22	1040	4.25	41	2	<2	9	31	<.2	1.3	1.2	36	.40	.068	29	24	.36	134	.027	<1	1.23	.013	.16	1	<1	4.9	1	<.01	3
351835	<.2	26	17	53	.2	24	12	348	2.94	32	1	<2	6	11	<.2	.9	<.5	26	.14	.055	31	16	.29	60	.012	<1	.88	.003	.06	2	<1	2.4	<1	<.01	2
351836	.4	26	19	68	.6	24	11	427	3.73	38	1	<2	3	9	<.2	.8	.5	27	.11	.093	25	18	.24	104	.008	<1	1.01	.003	.08	1	<1	2.0	<1	.02	3
351837	.2	22	20	72	.8	24	9	297	3.96	33	1	<2	4	7	<.2	.8	.7	27	.07	.083	22	24	.29	103	.008	<1	1.39	.002	.08	1	<1	1.8	<1	.02	3
351838	.2	34	22	69	.2	30	14	506	3.83	42	1	<2	7	5	<.2	<.5	.7	27	.04	.054	29	20	.30	71	.009	<1	1.22	.003	.09	2	<1	2.4	1	<.01	3
351839	<.2	6	12	17	.7	6	2	74	2.04	20	<1	<2	1	3	<.2	<.5	.5	23	.02	.080	21	11	.10	37	.008	1	.64	<.001	.04	1	<1	.6	<1	.01	3
351840	<.2	16	21	42	1.1	14	6	203	3.94	37	<1	<2	3	4	<.2	.8	.7	30	.04	.095	21	18	.21	45	.006	<1	.96	<.001	.05	1	<1	1.2	<1	.01	3
RE 351840	.2	15	21	41	1.1	14	6	201	3.88	36	<1	<2	3	4	<.2	.8	.7	27	.04	.093	21	18	.21	43	.006	<1	.95	<.001	.05	1	<1	1.1	<1	.01	3
351841	.3	19	15	48	.4	18	7	195	3.83	39	<1	<2	5	5	<.2	.8	<.5	24	.03	.048	23	17	.24	43	.005	<1	.93	.001	.05	1	<1	1.3	<1	.01	3
351843	<.2	10	17	35	.4	10	4	110	3.50	27	<1	<2	3	3	<.2	1.0	<.5	35	.03	.101	18	18	.17	44	.007	<1	1.05	<.001	.04	2	<1	1.1	<1	.02	3
351844	<.2	20	18	50	.8	20	7	203	4.02	34	1	<2	4	6	<.2	.6	<.5	21	.05	.091	21	21	.24	43	.007	1	1.15	<.001	.04	2	<1	1.4	<1	.02	3
351846	2.6	23	55	48	1.0	10	4	242	4.38	57	1	<2	2	28	<.2	1.3	.8	31	.13	.124	17	17	.08	98	.008	<1	.61	.003	.07	1	<1	1.1	<1	.06	3
351848	6.3	129	133	143	1.3	59	15	384	6.06	400	2	<2	2	42	<.2	55.2	2.1	45	.15	.105	19	12	.08	67	.006	<1	.63	<.001	.08	3	<1	5.1	<1	.05	1
351849	.3	21	22	53	.3	19	8	244	4.29	38	1	<2	3	8	<.2	1.2	<.5	26	.12	.150	20	19	.21	81	.009	<1	.89	<.001	.06	1	<1	1.4	<1	.02	3
351850	.2	24	21	61	.3	18	9	344	3.59	31	1	<2	2	8	<.2	1.0	<.5	30	.08	.080	20	18	.20	89	.008	<1	1.01	.001	.07	1	<1	1.2	<1	.01	3
00001	.5	41	17	88	.2	44	25	1917	4.09	31	2	<2	6	19	<.2	1.5	.8	26	.14	.076	21	21	.28	95	.025	<1	1.11	.005	.06	1	<1	4.7	1	.01	3
00002	.7	45	22	87	.3	46	19	858	3.70	32	2	<2	7	23	<.2	.6	.5	30	.32	.069	28	25	.49	179	.027	3	1.27	.007	.10	1	<1	4.2	1	<.01	3
00004	1.0	43	23	80	.3	47	19	930	3.38	30	2	<2	7	19	.2	1.1	.8	30	.27	.069	25	22	.43	165	.027	<1	1.14	.005	.08	1	<1	3.9	<1	.01	3
00005	.8	44	24	83	.3	45	19	796	3.59	34	2	<2	6	26	.2	.9	.7	30	.47	.065	27	24	.43	169	.027	<1	1.28	.007	.12	1	<1	4.1	<1	<.01	3
00006	.6	40	21	74	.3	42	17	734	3.17	23	2	<2	7	26	<.2	1.2	<.5	39	.36	.073	26	25	.46	176	.046	2	1.17	.009	.09	1	<1	4.2	<1	<.01	3
00007	1.8	56	21	98	1.2	40	14	818	3.19	24	4	<2	1	18	.4	1.4	<.5	36	.19	.082	26	30	.43	339	.016	<1	1.38	.002	.09	1	<1	3.6	<1	.01	3
00008	.7	42	32	66	.3	41	17	1040	3.84	45	1	<2	7	14	.2	.9	1.1	26	.12	.042	33	19	.34	222	.019	<1	1.29	.008	.15	2	<1	4.1	1	<.01	3
00009	.6	49	25	86	.3	49	20	991	3.74	30	2	<2	7	22	.2	1.2	.6	29	.29	.068	28	25	.49	189	.029	<1	1.27	.007	.11	1	<1	4.1	<1	<.01	3
00010	5.7	37	15	82	.5	39	10	475	2.43	24	3	<2	3	35	.3	2.7	<.5	35	.10	.057	22	20	.26	196	.027	<1	.89	.001	.05	1	<1	2.9	<1	<.01	2
00011	1.1	11	14	20	.6	5	1	43	2.44	7	<1	<2	3	3	<.2	1.1	<.5	23	.02	.025	15	16	.09	87	.016	3	.64	<.001	.02	1	<1	1.1	<1	<.01	3
00013	1.4	46	25	65	1.1	42	15	433	3.21	17	4	<2	3	21	.2	.9	<.5	33	.26	.067	24	31	.40	304	.020	1	1.74	.002	.06	1	<1	4.0	<1	.02	4
00014	2.7	47	21	71	1.8	35	12	709	3.14	29	5	<2	2	30	.2	1.3	.7	30	.34	.107	22	28	.34	434	.010	<1	1.33	.002	.09	1	<1	3.5	<1	.03	3
STANDARD C3	27.0	66	34	162	5.4	35	11	764	3.34	58	23	3	20	29	22.0	17.2	23.4	84	.57	.092	20	176	.60	159	.086	19	1.84	.039	.17	15	1	4.9	<1	.03	7
STANDARD G-2	1.6	3	5	44	<.1	7	4	559	2.08	<1	3	<2	5	101	<.2	<.5	<.5	43	.75	.102	11	87	.63	272	.134	6	1.28	.175	.61	2	<1	3.2	<1	<.01	5

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, MO, U = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM
- SAMPLE TYPE: SOIL SS80 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 24 2000 DATE REPORT MAILED: Nov 3/00 SIGNED BY ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00015	1.8	46	20	70	1.2	33	13	613	3.32	33	4	<2	4	23	<.2	1.3	.7	31	.28	.099	28	27	.35	350	.011	3	1.24	.005	.09	1	<1	3.5	<1	.02	3
00016	.7	66	18	120	.3	66	23	767	4.15	15	3	<2	8	40	.2	2.4	.5	59	.64	.080	23	37	.75	351	.072	<1	1.85	.019	.11	1	<1	5.8	<1	<.01	5
00017	.6	49	24	90	.3	46	17	675	3.68	31	2	<2	9	31	<.2	1.7	.6	30	.53	.071	29	27	.55	212	.035	4	1.29	.008	.09	1	<1	4.5	1	.03	4
00018	.6	47	22	89	.3	44	15	589	3.25	24	2	<2	9	37	<.2	1.8	1.0	31	.81	.071	28	25	.53	192	.040	3	1.27	.008	.08	1	<1	4.4	<1	<.01	4
00020	.3	49	28	86	.4	46	21	966	3.95	50	2	<2	10	26	<.2	2.2	.7	19	.32	.078	29	18	.30	68	.016	<1	.85	.004	.08	1	<1	3.7	<1	.03	3
00021	.2	43	24	90	.2	46	20	852	3.62	38	2	<2	13	29	<.2	2.0	.6	23	.43	.075	36	15	.27	63	.018	4	.74	.004	.07	2	<1	3.4	<1	.01	2
00022	.4	34	26	86	.4	35	22	451	3.06	24	2	<2	11	30	<.2	1.4	<.5	24	.24	.080	29	16	.21	92	.020	4	.94	.004	.07	1	<1	4.4	<1	.01	3
00023	.2	30	22	71	.4	29	13	535	3.37	27	1	<2	4	17	<.2	.8	.5	31	.21	.071	27	24	.40	98	.012	3	1.39	.003	.11	1	<1	2.8	<1	.01	4
00024	.3	59	36	93	.6	43	21	926	4.61	42	2	<2	5	29	<.2	1.2	1.3	33	.29	.123	25	30	.34	148	.007	1	1.98	.005	.16	2	<1	4.0	<1	.02	5
00025	<.2	23	18	54	.3	19	9	286	2.92	29	1	<2	4	14	<.2	.5	.5	25	.15	.059	25	15	.25	72	.006	<1	1.11	.002	.08	2	<1	1.8	<1	.01	3
00026	<.2	33	27	73	.2	28	11	368	5.13	42	1	<2	6	13	<.2	1.3	.9	32	.14	.069	25	23	.29	89	.009	<1	1.39	.003	.09	2	<1	2.2	<1	.01	4
00027	.2	19	20	48	.3	15	9	331	3.15	36	1	<2	4	14	<.2	1.4	1.2	24	.14	.067	25	15	.21	64	.006	<1	1.00	.002	.07	2	<1	1.4	<1	.01	3
00028	<.2	20	15	57	.3	17	8	313	3.27	35	1	<2	3	13	<.2	.9	1.1	24	.14	.070	24	14	.23	72	.005	<1	1.02	.001	.07	2	<1	1.6	<1	.01	3
00029	.2	26	16	67	.4	24	10	347	3.59	37	1	<2	4	19	<.2	1.0	1.4	24	.23	.084	25	16	.29	69	.006	<1	1.08	.002	.08	2	<1	2.0	<1	.01	3
00030	.2	33	19	70	.4	30	12	400	3.60	43	1	<2	4	17	<.2	1.6	1.7	24	.17	.078	26	17	.25	61	.006	2	.98	.001	.07	2	<1	2.3	<1	.01	3
RE 00030	.2	31	18	70	.4	29	12	393	3.62	43	1	<2	4	17	<.2	1.2	1.2	24	.17	.077	26	16	.25	61	.006	2	.98	.002	.07	2	<1	2.3	<1	.01	3
00031	.3	31	18	50	.7	25	10	331	2.95	30	1	<2	3	21	<.2	1.4	.5	25	.23	.073	25	17	.23	70	.007	<1	1.03	.001	.08	1	<1	2.4	<1	.01	3
00032	.6	16	17	47	.3	15	5	117	3.55	30	1	<2	5	13	<.2	1.3	<.5	24	.04	.176	23	17	.16	62	.007	<1	.88	<.001	.05	1	<1	1.3	<1	.01	3
00033	.4	30	21	80	.3	26	9	247	3.88	40	1	<2	6	24	<.2	1.8	<.5	24	.06	.150	27	19	.22	66	.007	<1	.86	.001	.07	2	<1	1.7	<1	.01	3
00034	.8	22	22	64	.4	18	5	137	4.00	40	1	<2	4	31	<.2	1.9	.5	31	.12	.098	20	18	.19	65	.006	<1	.83	<.001	.05	2	<1	1.3	<1	.02	2
00036	<.2	63	28	128	1.8	55	16	1492	5.20	74	6	<2	4	41	<.2	2.6	1.6	31	.61	.180	22	31	.30	179	.009	<1	2.17	.005	.18	2	<1	6.5	<1	.04	5
00037	.2	22	18	77	.3	20	10	397	3.54	52	1	<2	3	12	<.2	1.2	.6	25	.06	.072	23	18	.16	71	.006	<1	.98	<.001	.06	1	<1	1.5	<1	.01	3
00039	.2	23	25	62	.2	18	7	236	4.71	49	1	<2	6	11	<.2	1.6	.7	30	.05	.069	24	22	.20	90	.009	<1	1.00	<.001	.07	1	<1	1.8	<1	.01	4
00040	<.2	17	15	37	.2	14	7	349	2.06	31	1	<2	2	15	<.2	1.0	.5	17	.12	.062	22	11	.15	72	.007	<1	.65	.001	.07	1	<1	1.2	<1	.01	2
00041	<.2	27	18	58	.4	25	9	436	2.77	34	1	<2	3	13	<.2	1.1	<.5	23	.12	.071	28	18	.22	81	.008	<1	.96	.002	.08	1	<1	2.3	1	<.01	3
00042	.2	41	25	75	.4	39	16	629	3.65	46	2	<2	5	12	<.2	1.5	<.5	25	.13	.068	32	21	.36	86	.008	<1	1.36	.004	.11	2	<1	3.2	1	<.01	4
00043	<.2	23	22	61	.4	18	9	422	3.76	32	1	<2	4	6	<.2	1.0	<.5	32	.03	.085	24	21	.21	76	.008	<1	1.17	.001	.08	1	<1	1.6	1	.01	4
00044	<.2	35	19	64	.4	25	11	365	3.78	39	1	<2	5	7	<.2	.7	<.5	25	.05	.058	27	18	.28	57	.005	<1	1.17	.001	.07	2	<1	2.1	1	.01	3
00045	<.2	24	21	87	1.9	18	8	222	4.67	30	1	<2	8	6	<.2	1.4	<.5	31	.04	.062	22	24	.22	77	.004	<1	1.55	.002	.05	2	<1	2.1	1	.02	4
00046	<.2	22	13	65	.4	19	8	216	3.74	29	1	<2	4	13	<.2	1.2	<.5	25	.18	.097	25	19	.36	62	.005	<1	1.11	.001	.05	2	<1	1.5	<1	.01	4
00047	<.2	26	22	103	.4	25	11	306	5.19	37	2	<2	4	16	<.2	1.5	.5	38	.24	.121	21	25	.27	77	.008	<1	1.21	.002	.06	2	<1	1.9	<1	.02	5
00048	.5	45	19	78	.4	48	23	1760	3.75	36	2	<2	9	21	<.2	1.6	1.8	18	.23	.067	27	18	.27	84	.014	2	.99	.003	.06	2	<1	4.6	1	.01	3
00049	.5	30	21	68	.5	30	11	391	3.78	38	2	<2	4	23	<.2	1.5	.5	25	.23	.081	23	22	.27	115	.006	<1	1.30	.004	.10	2	<1	2.6	<1	.02	4
00050	<.2	36	26	76	.3	22	12	412	3.46	30	1	<2	9	8	<.2	1.1	<.5	26	.05	.064	28	22	.22	99	.008	<1	1.33	.004	.09	2	<1	3.1	<1	<.01	4
STANDARD C3	26.0	63	34	164	5.2	34	11	759	3.17	60	23	2	21	29	21.7	18.6	23.4	72	.58	.093	20	173	.60	158	.085	23	1.81	.039	.17	14	1	4.6	<1	.03	7
STANDARD G-2	1.6	3	4	45	<.1	7	4	566	2.14	<1	3	<2	5	89	<.2	<.5	<.5	45	.72	.105	11	83	.64	259	.135	2	1.12	.137	.56	2	<1	3.1	<1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00051	.6	32	30	81	.1	26	10	369	4.77	40	1	<2	2	11	.2	<.5	<.5	33	.17	.122	25	24	.26	113	.011	1	1.19	.002	.09	2	<1	1.5	<1	.02	3
00052	.3	33	23	79	.2	28	11	332	4.48	33	1	<2	5	11	<.2	<.5	<.5	36	.14	.061	28	25	.36	112	.010	1	1.45	.001	.08	2	<1	2.0	<1	.01	3
00053	<.2	19	17	58	.2	17	7	287	3.00	25	1	<2	2	11	<.2	<.5	<.5	29	.14	.067	26	17	.28	79	.009	<1	1.01	<.001	.07	2	<1	1.2	<1	.01	3
00054	.4	36	23	75	.4	29	14	886	3.66	30	2	<2	3	16	<.2	<.5	.6	29	.16	.081	27	23	.32	106	.009	1	1.30	.001	.10	2	<1	2.4	<1	.02	3
00057	<.2	39	23	75	.3	32	18	521	3.99	38	2	<2	5	16	<.2	.8	.8	24	.16	.060	31	18	.36	71	.005	<1	1.28	<.001	.06	6	<1	2.3	<1	.01	3
00058	.4	23	20	53	.2	17	6	172	3.37	31	1	<2	3	17	<.2	.7	<.5	29	.19	.055	31	12	.13	80	.010	<1	.62	<.001	.05	2	<1	1.2	<1	.01	3
00059	.4	25	21	59	.6	20	10	453	3.13	27	2	<2	2	21	<.2	<.5	<.5	24	.29	.060	28	15	.23	88	.006	<1	1.00	<.001	.06	2	<1	1.5	<1	.01	3
00060	1.2	33	49	72	.8	18	6	164	4.74	29	1	<2	4	37	<.2	.7	<.5	24	.06	.084	28	15	.18	91	.005	1	.77	<.001	.04	3	<1	1.1	<1	.04	2
00061	.3	15	17	39	.2	10	4	115	2.73	22	<1	<2	3	5	<.2	<.5	<.5	29	.04	.039	26	10	.10	55	.009	1	.62	<.001	.04	2	<1	.8	<1	.01	3
00062	.3	27	18	51	.2	15	6	215	2.82	26	1	<2	7	11	<.2	<.5	.5	32	.11	.040	30	16	.12	67	.008	<1	.99	<.001	.06	1	<1	1.7	<1	<.01	3
00064	.2	59	31	82	.7	42	18	700	4.29	39	3	<2	7	14	<.2	<.5	2.1	26	.16	.067	34	21	.36	94	.005	<1	1.66	<.001	.10	2	<1	4.2	<1	.01	3
00065	.5	85	37	106	1.4	58	23	1723	5.33	46	5	<2	6	27	.3	<.5	2.7	32	.33	.123	35	27	.37	141	.006	<1	2.17	.002	.16	3	<1	6.0	<1	.03	4
RE 00065	.5	82	37	102	1.3	55	22	1658	5.15	44	5	<2	6	27	.3	<.5	2.3	31	.32	.120	34	27	.36	140	.006	<1	2.10	.002	.16	3	<1	5.9	<1	.03	4
00067	.4	30	28	66	.1	19	9	377	4.66	35	1	<2	6	8	<.2	<.5	<.5	36	.08	.075	31	18	.20	95	.012	<1	1.03	<.001	.06	3	<1	1.8	<1	.01	3
00068	.3	19	20	42	.2	14	6	217	2.97	32	1	<2	2	11	<.2	<.5	<.5	30	.08	.056	27	14	.16	64	.007	<1	.86	<.001	.04	3	<1	1.0	<1	<.01	3
00069	.3	44	21	66	.6	31	16	573	3.90	42	2	<2	3	18	<.2	.5	.5	26	.22	.078	28	18	.26	69	.006	<1	1.26	<.001	.07	2	<1	2.5	<1	.01	3
00072	6.5	25	232	18	4.7	1	<1	10	2.02	620	<1	3	4	15	.2	13.1	70.4	20	.01	.036	11	5	.01	38	<.001	1	.11	<.001	.04	2	<1	.9	<1	.14	<1
00073	7.4	26	257	20	5.6	2	<1	19	2.14	678	1	5	4	17	.2	14.0	71.7	20	.01	.042	12	6	.01	39	<.001	<1	.13	<.001	.04	3	<1	1.0	<1	.15	<1
00074	7.5	33	271	21	5.7	1	<1	10	2.51	796	<1	4	4	16	.2	14.3	90.8	22	.01	.048	12	6	.01	35	<.001	1	.11	<.001	.04	3	<1	1.0	<1	.14	<1
00075	6.2	95	326	148	13.8	26	4	323	8.61	1575	1	63	3	28	1.0	9.7	32.6	33	.04	.118	10	17	.03	46	<.001	<1	.16	<.001	.07	7	1	3.6	1	.36	<1
00076	.6	19	13	35	.6	15	5	177	3.30	42	<1	<2	3	6	<.2	1.0	.9	16	.02	.066	25	11	.15	18	.004	<1	.54	<.001	.03	2	<1	1.0	<1	.04	2
00077	.4	27	20	40	.6	14	5	146	2.95	41	1	<2	2	7	<.2	<.5	.6	22	.06	.113	23	14	.20	29	.004	1	.75	<.001	.04	1	<1	1.2	<1	.02	2
00078	.3	46	18	58	.3	25	11	375	3.44	37	1	<2	3	8	<.2	<.5	<.5	25	.08	.080	28	19	.29	45	.007	<1	1.06	<.001	.05	2	<1	1.8	<1	.02	3
00079	<.2	34	17	53	.6	20	8	271	2.93	30	1	<2	2	8	<.2	.7	<.5	26	.07	.064	25	17	.23	48	.007	<1	1.06	<.001	.05	1	<1	1.5	<1	.01	3
00082	8.4	19	72	56	4.0	19	4	158	4.89	142	2	<2	4	100	<.2	18.9	.8	11	.07	.240	13	9	.04	226	.002	1	.27	<.001	.10	2	1	2.5	1	.18	<1
00083	.4	43	28	100	.2	66	19	1208	3.92	49	2	<2	13	34	.2	.7	.8	18	.87	.058	35	17	.39	78	.006	<1	.99	<.001	.13	1	<1	3.3	<1	<.01	2
00084	1.4	68	26	92	.4	51	22	938	4.15	43	2	<2	10	38	<.2	1.0	1.3	26	.73	.070	28	22	.37	103	.018	1	1.05	<.001	.08	2	<1	4.2	<1	.02	3
00085	1.6	61	17	102	.3	48	16	493	4.00	30	3	<2	9	27	<.2	1.9	1.2	24	.21	.078	27	18	.20	88	.023	<1	.79	<.001	.04	1	<1	3.7	<1	.01	2
00089	1.1	42	17	80	.2	42	16	646	3.24	24	2	<2	7	21	.2	.8	.5	45	.28	.070	24	29	.52	206	.062	2	1.16	.002	.06	1	<1	4.6	<1	<.01	3
00090	1.0	44	21	83	.3	46	17	703	3.62	15	2	<2	10	18	<.2	<.5	<.5	42	.21	.053	27	28	.43	146	.064	<1	1.36	<.001	.04	1	<1	5.4	<1	<.01	3
00091	.8	43	16	79	.3	42	16	545	3.40	23	2	<2	7	29	<.2	<.5	<.5	52	.37	.078	23	33	.59	230	.078	1	1.41	.004	.07	1	<1	5.2	<1	<.01	4
00092	25.2	70	29	39	2.3	15	<1	25	2.74	104	2	<2	6	18	<.2	9.5	<.5	18	.01	.037	12	12	.01	334	.002	1	.17	<.001	.03	1	<1	1.8	<1	.03	<1
00094	1.6	19	14	43	.4	15	5	171	2.25	25	2	<2	2	12	<.2	1.4	.8	22	.14	.039	24	18	.18	179	.009	1	.71	<.001	.05	2	<1	1.2	<1	.01	2
00095	1.6	25	17	55	.4	21	9	424	2.54	32	2	<2	2	11	<.2	.7	1.1	24	.12	.041	27	20	.22	191	.010	1	.83	<.001	.05	2	<1	1.8	1	.01	2
STANDARD C3	25.9	63	34	164	5.4	34	11	764	3.23	57	25	2	20	29	21.8	15.3	22.1	80	.57	.093	20	172	.60	155	.092	21	1.81	.033	.16	16	1	4.5	<1	.03	7
STANDARD G-2	1.5	3	2	44	<.1	7	4	565	2.10	<1	3	<2	5	75	<.2	<.5	<.5	43	.68	.101	11	82	.63	239	.148	4	.96	.076	.48	2	<1	2.7	<1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00101	.8	47	19	75	.3	49	24	1690	3.95	37	2	<2	8	21	<.2	1.1	1.6	21	.23	.067	26	18	.27	78	.012	<1	.88	<.001	.04	3	<1	4.6	1	.01	2
00102	.6	44	27	75	.2	43	18	774	3.88	46	1	<2	10	77	<.2	<.5	.8	26	2.03	.062	30	25	.49	158	.014	1	1.17	.003	.18	2	<1	4.4	<1	<.01	3
00103	.7	30	30	74	.4	29	14	503	4.59	41	1	<2	3	17	.2	.6	.5	28	.14	.092	24	22	.25	92	.008	<1	1.06	<.001	.07	2	<1	2.0	<1	.02	3
00104	.8	38	30	81	2.3	36	15	1222	4.14	41	2	<2	2	17	.3	.6	.5	28	.19	.120	20	23	.24	131	.007	1	1.22	<.001	.11	2	<1	2.2	<1	.03	3
00105	1.7	85	39	110	3.4	79	23	2847	6.19	59	4	<2	6	33	.8	1.3	1.1	36	.35	.188	29	34	.34	170	.006	2	2.38	.004	.19	2	<1	7.5	2	.05	5
00106	.4	25	19	59	.1	27	11	371	3.32	36	1	<2	4	12	<.2	<.5	<.5	18	.15	.061	29	15	.26	65	.005	<1	.88	<.001	.06	2	<1	1.8	<1	.01	2
00107	.7	20	21	51	.2	19	8	249	3.81	41	1	<2	3	6	<.2	.7	<.5	20	.06	.066	22	17	.22	57	.004	<1	.89	<.001	.04	2	<1	1.2	<1	.02	2
00108	.7	28	26	60	.2	29	10	324	4.13	42	1	<2	5	8	<.2	.8	<.5	21	.09	.079	24	19	.27	64	.005	<1	.96	<.001	.05	2	<1	1.6	<1	.02	2
00109	.6	18	20	54	.2	18	7	209	4.18	35	<1	<2	7	8	<.2	.5	<.5	25	.04	.062	26	20	.20	52	.005	<1	.99	<.001	.04	2	<1	1.5	1	.01	3
00110	.7	17	15	49	.4	16	7	210	4.11	34	<1	<2	4	8	<.2	<.5	<.5	30	.04	.162	26	18	.19	63	.009	<1	.86	<.001	.04	2	<1	1.2	<1	.01	3
00111	1.3	33	17	67	1.4	22	6	157	4.29	41	2	<2	3	92	<.2	1.5	2.0	35	.05	.272	20	23	.15	61	.007	1	.76	<.001	.04	2	<1	1.6	<1	.03	2
00112	.8	18	11	43	1.2	14	4	125	2.16	17	1	<2	1	14	<.2	.7	.7	22	.06	.151	19	9	.05	33	.004	1	.46	<.001	.03	2	<1	.5	<1	.02	2
00113	1.0	32	26	63	.2	25	8	230	4.40	63	1	<2	3	14	<.2	1.0	1.7	40	.06	.132	27	18	.12	45	.009	<1	.63	<.001	.04	3	<1	1.3	<1	.02	3
00114	1.5	49	29	109	.8	38	9	306	3.94	65	1	<2	2	45	<.2	2.5	3.3	38	.09	.133	18	26	.13	69	.002	2	.90	<.001	.06	3	<1	2.3	<1	.03	2
00116	.6	11	9	27	<.1	9	4	414	1.81	30	<1	<2	1	6	<.2	<.5	1.0	24	.03	.058	28	9	.04	51	.006	<1	.62	<.001	.03	2	<1	.5	1	<.01	3
00117	.9	25	19	66	.5	23	10	434	4.12	52	1	<2	3	14	<.2	<.5	3.6	31	.09	.105	22	21	.22	73	.007	<1	1.09	<.001	.07	4	<1	1.5	<1	.02	3
00118	1.0	22	20	36	.3	17	5	139	3.69	38	1	<2	2	10	<.2	.8	.7	29	.05	.138	20	15	.10	50	.007	<1	.71	<.001	.04	2	<1	.9	<1	.03	2
00119	.3	16	20	39	.2	14	5	163	3.54	30	1	<2	2	5	<.2	<.5	<.5	32	.05	.084	23	15	.17	65	.007	<1	.84	<.001	.04	3	<1	1.2	<1	.02	3
00120	.5	20	17	55	.1	18	8	244	3.31	28	1	<2	2	15	<.2	<.5	<.5	33	.18	.053	27	16	.19	123	.008	<1	.92	<.001	.05	2	<1	1.4	<1	.01	3
RE 00120	.5	18	18	53	.1	17	8	239	3.23	27	1	<2	2	14	<.2	<.5	<.5	31	.18	.052	27	16	.19	120	.008	<1	.91	<.001	.05	2	<1	1.3	<1	.01	3
00121	.2	12	15	32	.1	11	4	144	2.99	24	<1	<2	2	4	<.2	.5	<.5	22	.05	.045	26	12	.14	62	.005	<1	.66	<.001	.04	3	<1	.8	<1	.01	2
00122	.3	13	17	38	.3	10	4	217	2.58	20	<1	<2	2	7	<.2	<.5	<.5	25	.06	.052	25	12	.10	87	.007	<1	.79	<.001	.04	2	<1	.9	<1	.01	3
00123	.4	21	18	45	.2	14	6	142	4.27	30	<1	<2	7	4	<.2	<.5	<.5	20	.03	.051	29	17	.19	44	.004	1	.95	<.001	.04	3	<1	1.3	<1	.01	2
00124	.4	20	21	56	.2	17	7	177	4.53	33	1	<2	6	5	<.2	<.5	<.5	19	.05	.078	28	14	.20	38	.003	<1	.74	<.001	.03	4	<1	1.4	<1	.01	1
00125	.3	29	24	68	.8	22	11	1467	3.52	30	3	<2	2	18	<.2	<.5	<.5	24	.27	.105	22	15	.21	73	.005	<1	1.03	<.001	.05	2	<1	2.1	<1	.02	3
00126	.6	44	29	53	.2	19	6	115	3.15	19	1	<2	3	14	<.2	.6	<.5	33	.05	.074	27	11	.09	40	.006	<1	.60	<.001	.02	2	<1	1.2	<1	.01	3
00127	.9	27	16	57	.6	17	4	97	2.49	14	1	<2	2	13	<.2	.6	<.5	33	.04	.062	31	10	.03	50	.005	1	.43	<.001	.02	2	<1	.8	1	.01	2
00128	.5	20	12	73	.6	20	9	276	3.12	22	1	<2	3	12	<.2	<.5	<.5	26	.14	.076	24	18	.30	65	.004	1	1.12	<.001	.05	4	<1	1.7	<1	.02	3
00129	.6	27	17	61	.9	23	11	541	3.14	29	1	<2	3	13	<.2	<.5	<.5	25	.15	.065	22	17	.25	87	.004	<1	1.11	<.001	.07	3	<1	1.6	<1	.02	3
00130	.6	51	26	67	.5	35	15	738	3.76	36	2	<2	4	17	<.2	.8	<.5	24	.19	.075	26	20	.27	78	.004	1	1.19	<.001	.08	3	<1	2.5	<1	.02	3
00131	.8	44	24	77	.6	33	13	677	3.96	40	2	<2	2	18	<.2	.6	<.5	26	.18	.086	23	20	.25	111	.005	<1	1.13	<.001	.08	3	<1	1.8	<1	.02	3
00132	.5	30	23	68	.2	26	13	540	4.15	36	1	<2	2	10	<.2	.6	<.5	29	.11	.080	24	20	.28	74	.009	<1	1.04	<.001	.07	2	<1	1.6	<1	.01	3
00134	.5	14	20	30	.1	9	3	114	1.79	34	<1	<2	1	11	<.2	1.2	1.0	21	.06	.077	22	9	.07	70	.004	1	.45	<.001	.05	2	<1	.6	<1	.01	2
00135	.7	23	28	60	.1	21	7	197	3.68	52	1	<2	2	15	<.2	1.9	.9	25	.10	.143	23	18	.21	92	.005	<1	.75	<.001	.06	2	<1	1.1	<1	.01	2
STANDARD C3	27.4	68	40	165	5.3	36	12	812	3.44	61	23	2	20	30	22.8	14.7	22.9	87	.61	.098	19	185	.64	165	.088	23	1.81	.034	.17	15	1	4.8	<1	.03	7
STANDARD G-2	1.5	3	2	43	<.1	7	4	561	2.09	<1	3	<2	4	76	<.2	<.5	<.5	45	.69	.105	10	83	.63	239	.135	<1	.92	.074	.48	3	<1	2.9	2	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Date ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00136	.7	23	23	68	.1	20	7	232	3.65	40	1	<2	2	14	<.2	.9	.9	30	.11	.084	25	18	.18	98	.009	1	.83	.001	.06	2	<1	1.1	<1	.01	3
00138	1.1	46	31	78	1.0	40	17	757	3.86	152	2	5	6	17	.3	.9	2.6	22	.15	.067	32	17	.30	69	.005	3	.96	.001	.08	2	<1	2.9	<1	.01	2
00139	.6	14	15	52	.5	14	5	185	2.74	28	1	<2	2	11	<.2	.6	<.5	24	.05	.074	22	18	.18	63	.006	2	.83	<.001	.05	2	<1	1.0	<1	.01	2
00140	.6	21	18	67	1.0	21	7	382	3.35	37	1	3	2	9	<.2	.7	.9	28	.05	.077	24	21	.22	82	.007	3	.98	<.001	.07	2	<1	1.2	<1	.01	3
00141	.5	18	16	47	.3	17	6	194	2.91	33	1	<2	3	7	<.2	<.5	.5	31	.05	.067	25	18	.20	73	.007	1	.75	<.001	.05	2	<1	1.0	<1	.01	2
00142	.5	12	17	42	.1	13	5	149	3.35	30	1	<2	5	5	<.2	.5	<.5	32	.04	.063	24	20	.18	73	.010	<1	.82	<.001	.05	2	<1	1.3	<1	.01	3
00143	.3	16	14	46	.2	18	6	217	3.00	25	1	<2	3	7	<.2	<.5	<.5	36	.10	.058	23	20	.28	64	.024	<1	.90	<.001	.06	2	<1	1.4	<1	.01	3
00144	.2	17	15	48	.3	16	6	244	3.25	23	1	<2	2	6	<.2	<.5	<.5	29	.08	.054	23	22	.25	75	.014	2	1.04	<.001	.06	2	<1	1.2	<1	.02	3
00145	.4	19	16	46	.1	15	6	193	3.23	27	1	<2	2	5	<.2	<.5	<.5	27	.05	.044	25	18	.24	81	.007	1	1.02	<.001	.06	2	<1	1.2	<1	.01	3
00146	.3	24	16	44	.3	16	8	328	2.50	21	1	<2	1	8	<.2	<.5	.5	25	.07	.050	26	18	.19	98	.007	1	1.16	<.001	.09	2	<1	1.6	<1	.01	3
00147	.3	12	11	33	.1	11	4	145	2.07	18	1	<2	2	7	<.2	<.5	.6	18	.08	.051	22	14	.16	92	.006	<1	.83	<.001	.07	2	<1	.9	<1	.01	2
00148	.3	25	15	56	.1	21	8	245	3.40	30	1	<2	7	9	<.2	<.5	.7	23	.07	.050	28	20	.27	90	.007	1	1.20	<.001	.09	2	<1	1.9	<1	.01	3
00150	.3	37	17	98	.8	43	11	522	3.14	25	3	<2	3	23	.2	<.5	.5	22	.32	.110	32	21	.27	138	.005	<1	1.61	<.001	.09	3	<1	4.0	<1	.03	3
RE 00150	.4	38	17	101	.8	44	11	528	3.22	25	3	<2	3	23	.2	<.5	.8	22	.33	.111	33	22	.28	141	.005	1	1.66	.002	.10	2	<1	4.0	<1	.03	3
00151	.2	63	18	29	1.8	43	6	186	1.96	37	19	<2	2	108	.6	<.5	.6	14	2.07	.169	19	20	.27	102	.007	1	1.28	.004	.06	1	<1	3.2	<1	.30	1
00152	.7	49	30	84	.2	35	18	493	3.48	44	2	<2	11	20	<.2	1.0	.7	25	.31	.065	35	17	.38	80	.008	<1	1.04	<.001	.08	3	<1	4.0	<1	.01	2
00153	.5	43	26	79	.2	42	17	796	3.40	28	2	<2	11	48	<.2	<.5	.7	25	1.12	.062	29	22	.44	107	.015	2	1.05	.001	.13	2	<1	4.0	<1	<.01	3
00154	.6	41	19	76	.2	38	17	594	3.44	24	2	<2	11	28	<.2	1.1	.5	18	.44	.060	29	14	.25	58	.018	1	.67	<.001	.04	2	<1	3.1	<1	.01	2
00155	.6	45	26	88	.2	46	19	896	3.58	34	2	<2	12	26	.3	.7	.7	21	.39	.068	29	17	.34	78	.014	2	.82	<.001	.08	2	<1	3.2	<1	.02	2
00156	.9	52	35	93	.3	50	20	879	4.08	38	2	<2	10	22	.2	.9	.8	23	.25	.064	27	20	.34	129	.015	3	.90	<.001	.07	3	<1	3.8	<1	.02	2
00157	1.7	47	11	91	.5	49	15	546	2.96	12	4	<2	6	22	.3	1.1	<.5	51	.28	.082	21	31	.48	266	.080	2	1.22	.003	.05	<1	<1	3.8	<1	<.01	3
00158	2.0	51	14	91	.6	49	15	532	2.99	17	4	<2	6	19	.3	1.7	<.5	50	.21	.078	22	30	.43	235	.069	1	1.25	.001	.06	1	<1	3.6	<1	<.01	3
00160	1.7	53	13	102	.8	56	17	502	3.18	16	5	<2	6	25	.3	1.3	<.5	58	.30	.081	23	36	.53	360	.084	2	1.49	.005	.06	1	<1	4.5	<1	<.01	4
00161	1.5	55	13	229	2.5	135	19	471	2.88	14	6	<2	5	29	.4	1.2	<.5	53	.34	.087	19	38	.58	401	.097	1	1.76	.006	.07	<1	<1	4.9	<1	<.01	4
00162	2.2	29	17	65	.5	29	10	438	2.66	27	1	<2	4	8	.2	1.3	<.5	28	.06	.059	23	23	.28	122	.020	<1	1.05	<.001	.08	2	<1	2.0	<1	<.01	2
00163	3.8	97	14	156	.8	74	32	420	3.30	20	8	<2	5	21	.5	2.1	<.5	44	.18	.089	20	28	.36	451	.076	<1	1.19	<.001	.05	1	<1	4.2	<1	.01	3
00164	3.8	95	14	156	.8	74	31	427	3.30	21	8	<2	6	21	.5	2.3	<.5	43	.18	.089	21	28	.36	466	.075	2	1.19	<.001	.05	1	<1	4.3	<1	.01	3
00165	4.0	101	14	165	.8	78	33	436	3.40	21	8	<2	5	21	.6	1.9	<.5	44	.18	.093	20	28	.37	463	.079	<1	1.22	<.001	.05	1	<1	4.4	<1	.01	3
00166	3.8	98	14	158	.8	75	32	457	3.34	21	8	<2	5	21	.6	2.0	<.5	42	.18	.088	21	28	.36	467	.076	<1	1.18	<.001	.05	1	<1	4.3	<1	.01	3
00167	3.1	66	13	120	.6	57	14	417	3.13	22	6	<2	7	14	.4	1.8	<.5	42	.17	.072	24	26	.28	288	.062	<1	.82	<.001	.03	1	<1	3.0	<1	<.01	2
00170	.4	37	15	73	.1	34	16	416	3.03	14	2	<2	11	17	<.2	1.0	<.5	20	.16	.052	31	15	.19	68	.030	<1	.65	<.001	.03	1	<1	3.2	<1	<.01	2
00171	.5	45	26	78	.3	37	17	647	3.50	36	2	<2	7	35	.2	.8	.6	24	.65	.076	29	21	.38	84	.013	3	1.04	<.001	.08	2	<1	3.7	<1	.03	2
00172	.4	43	23	75	.1	41	18	738	3.65	38	2	<2	11	42	.2	<.5	1.0	19	.88	.068	27	18	.42	59	.012	1	.88	<.001	.07	2	<1	3.0	<1	.02	2
00173	.9	49	38	103	2.6	57	17	2021	4.40	46	7	<2	5	30	.4	<.5	1.2	33	.41	.143	31	34	.30	203	.010	<1	2.37	.002	.15	2	<1	5.9	<1	.05	4
STANDARD C3	26.2	63	36	165	5.3	36	11	771	3.25	58	26	<2	20	30	21.9	13.6	22.9	81	.58	.095	21	174	.60	158	.086	22	1.82	.036	.16	15	1	4.5	<1	.03	6
STANDARD G-2	1.4	2	2	42	<.1	7	3	513	1.93	<1	4	<2	5	69	<.2	<.5	<.5	39	.62	.101	9	77	.58	224	.119	1	.87	.070	.45	3	<1	2.5	<1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00174	.6	41	25	81	.5	35	15	779	4.18	36	2	<2	4	26	<.2	.9	.8	33	.34	.090	27	29	.35	147	.007	2	1.61	.003	.13	2	<1	3.4	<1	.02	3
00175	.4	37	23	80	.6	35	15	880	3.85	36	2	<2	3	21	.2	.5	.7	27	.23	.084	27	24	.30	119	.007	1	1.35	.001	.10	2	<1	3.0	<1	.02	3
00176	.3	33	21	79	.6	31	12	756	3.58	33	2	<2	2	20	<.2	.5	<.5	27	.26	.083	25	21	.28	127	.006	2	1.28	.001	.10	2	<1	2.6	<1	.03	2
00177	.4	25	18	72	.3	24	11	445	3.47	32	1	<2	3	11	<.2	.7	<.5	26	.11	.065	29	21	.28	109	.005	<1	1.22	<.001	.08	2	<1	2.1	<1	.01	3
00178	.4	37	23	77	.7	35	14	915	3.82	40	2	<2	3	21	.2	.6	.6	27	.27	.085	25	21	.29	110	.007	<1	1.24	<.001	.11	3	<1	2.9	<1	.02	2
00179	.5	37	23	82	.8	37	14	929	3.94	41	2	<2	3	24	<.2	.5	.5	28	.28	.088	26	22	.31	122	.006	1	1.32	.001	.12	2	<1	3.4	<1	.02	3
00180	.4	18	16	44	.4	14	6	164	2.59	25	1	<2	2	7	<.2	.5	<.5	25	.07	.044	26	14	.24	66	.005	1	.85	<.001	.06	2	<1	1.2	<1	.02	2
00181	.3	27	20	64	.2	26	14	461	3.41	36	1	<2	6	8	<.2	<.5	<.5	22	.10	.046	35	15	.29	65	.005	3	.89	<.001	.06	2	<1	1.8	<1	<.01	2
00182	.2	17	14	48	.1	17	6	217	3.08	27	1	<2	3	10	<.2	<.5	<.5	33	.14	.049	29	20	.23	102	.010	1	.89	<.001	.07	2	<1	1.4	<1	<.01	3
00183	.4	21	16	54	.1	24	13	486	3.06	27	1	<2	3	10	<.2	.7	<.5	30	.16	.048	29	22	.35	81	.013	2	1.03	<.001	.07	1	<1	1.9	<1	<.01	3
00184	.4	30	23	83	.2	33	13	448	3.97	42	2	<2	3	16	<.2	<.5	<.5	32	.18	.067	26	24	.28	128	.008	2	1.26	<.001	.09	2	<1	2.3	<1	.01	3
00185	.4	35	27	95	.5	47	19	1277	4.01	56	2	<2	3	27	<.2	.5	1.0	29	.34	.123	23	23	.33	142	.010	<1	1.28	<.001	.11	2	<1	3.4	<1	.03	3
RE 00185	.4	36	28	97	.5	48	20	1326	4.17	59	3	<2	3	27	.2	.5	.9	30	.35	.125	24	24	.35	145	.010	1	1.32	<.001	.12	2	<1	3.5	<1	.03	3
00186	.8	37	37	73	.4	42	17	728	4.67	142	2	<2	5	11	.3	.9	1.5	27	.12	.057	32	18	.26	69	.009	<1	.94	<.001	.08	3	<1	2.6	<1	.02	2
00187	.8	33	38	85	.5	57	21	790	5.18	178	3	<2	4	25	.3	1.3	3.5	24	.10	.077	26	18	.17	64	.004	<1	.74	<.001	.06	3	<1	3.0	<1	.03	2
00189	.7	41	28	87	<.1	36	17	482	4.31	86	1	<2	8	8	<.2	<.5	.7	17	.02	.044	35	16	.27	48	.003	<1	.95	<.001	.06	5	<1	2.1	1	.02	1
00190	.4	15	16	48	.2	16	6	203	3.69	30	1	<2	2	5	<.2	<.5	<.5	27	.06	.104	26	20	.23	67	.009	<1	.93	<.001	.05	2	<1	1.2	<1	.01	2
00191	.6	14	18	44	.4	15	5	174	3.57	33	<1	<2	3	6	<.2	<.5	.5	30	.04	.097	27	18	.16	58	.009	<1	.77	<.001	.05	2	<1	1.0	1	.01	3
00192	.5	12	15	28	.3	8	3	124	2.45	24	1	<2	1	8	.2	.5	<.5	33	.05	.098	23	13	.09	97	.007	<1	.62	<.001	.04	2	<1	.6	<1	.02	3
00193	.5	26	20	66	.2	27	10	269	4.20	34	1	<2	7	5	<.2	.7	<.5	24	.04	.086	35	25	.39	60	.004	1	1.20	<.001	.06	2	<1	1.9	<1	.01	3
00195	.8	36	26	80	1.2	30	7	170	4.35	23	1	<2	3	17	<.2	.7	<.5	25	.03	.112	23	17	.14	42	.002	<1	.70	<.001	.03	2	<1	1.4	<1	.03	1
00196	.8	23	20	65	.1	21	6	138	3.33	22	1	<2	2	9	<.2	.5	<.5	36	.05	.069	26	14	.12	54	.007	<1	.70	<.001	.04	2	<1	1.2	<1	.02	4
00198	1.0	93	36	85	.5	32	9	228	5.26	29	2	<2	3	14	<.2	1.4	<.5	30	.05	.136	23	16	.12	55	.004	<1	.77	<.001	.03	2	<1	1.6	<1	.02	2
00199	.4	14	19	41	.2	12	5	149	3.31	22	1	<2	2	5	<.2	.5	<.5	33	.04	.066	24	16	.15	50	.008	<1	.79	<.001	.03	2	<1	1.0	<1	.01	3
00200	.2	14	18	51	.3	17	7	202	4.21	22	1	<2	4	4	<.2	<.5	<.5	31	.05	.053	24	27	.36	65	.007	<1	1.16	<.001	.04	2	<1	1.6	<1	.01	3
00201	<.2	16	15	61	.2	22	11	321	3.87	25	1	<2	5	9	<.2	.8	<.5	29	.10	.049	29	28	.47	51	.005	1	1.31	<.001	.04	2	<1	1.8	<1	.01	3
00202	.2	43	25	87	1.0	37	15	1249	4.29	26	4	<2	4	33	.3	.5	<.5	30	.56	.109	27	29	.42	95	.008	<1	1.66	<.001	.08	1	<1	3.6	<1	.04	4
00203	.2	24	23	74	.2	26	15	526	3.82	27	2	<2	6	15	<.2	<.5	<.5	33	.22	.044	28	30	.46	82	.006	<1	1.47	<.001	.05	2	<1	2.6	<1	.01	4
00204	1.5	23	95	76	1.0	18	7	191	4.96	75	1	<2	4	6	<.2	.6	12.0	35	.07	.054	24	18	.15	84	.011	1	.81	<.001	.04	2	<1	1.2	<1	.02	3
00205	.4	23	20	90	.1	29	14	466	3.92	37	1	<2	5	9	<.2	.5	<.5	26	.12	.052	27	21	.27	80	.007	<1	1.03	<.001	.05	2	<1	1.8	<1	.01	2
00206	.4	24	23	69	.2	28	12	398	3.53	31	2	<2	4	14	<.2	.8	.5	20	.19	.065	23	18	.29	74	.005	<1	.98	<.001	.06	2	<1	2.1	1	.02	2
00207	.8	21	17	65	.2	23	11	406	3.22	28	3	<2	4	15	<.2	.8	<.5	21	.21	.052	25	17	.30	67	.006	<1	.89	<.001	.05	2	<1	2.0	<1	.02	2
STANDARD C3	26.9	67	36	172	5.4	37	12	816	3.49	60	27	3	21	30	22.6	14.0	23.5	85	.61	.097	22	181	.64	162	.087	21	1.81	.035	.17	16	1	4.8	<1	.03	7
STANDARD G-2	1.5	3	2	43	<.1	7	3	539	2.02	<1	3	<2	4	73	<.2	.6	<.5	41	.66	.101	11	78	.60	228	.128	<1	.88	.071	.46	3	<1	2.7	1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004307R Page 1

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: K. Ross

SAMPLE#	Au* ppb
351823	26.1
351824	6.3
351825	12.4
351828	55.3
351829	235.2
351832	221.0
351833	52.3
351834	66.3
351835	124.8
351836	92.5
351837	65.7
351838	82.7
351839	267.0
351840	132.8
RE 351840	191.0
351841	51.5
351843	117.0
351844	51.7
351846	50.8
351848	433.1
351849	89.8
351850	44.0
00001	74.4
00002	41.1
00004	59.4
00005	51.7
00006	34.0
00007	22.2
00008	111.0
00009	89.8
00010	17.4
00011	46.8
00013	51.6
00014	31.1
STANDARD DS2	205.6

AU* BY ACID LEACHED, ANALYSIS BY ICP/MS. (10 gm)
- SAMPLE TYPE: SOIL PULP
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: NOV 23 2000 DATE REPORT MAILED: Nov 27/00 SIGNED BY. ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA

SAMPLE#	Au* ppb
00015	258.2
00016	5.7
00017	72.9
00018	23.3
00020	221.5
00021	115.3
00022	54.4
00023	59.6
00024	48.6
00025	27.6
00026	74.4
00027	94.7
00028	130.6
00029	57.9
00030	103.5
RE 00030	200.8
00031	51.7
00032	42.0
00033	82.5
00034	59.8
00036	113.1
00037	69.3
00039	124.9
00040	197.9
00041	52.3
00042	21.9
00043	9.1
00044	44.1
00045	27.9
00046	10.8
00047	145.1
00048	215.2
00049	137.1
00050	44.9
STANDARD DS2	203.1

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au* ppb
00051	16.4
00052	10.0
00053	13.3
00054	10.7
00057	110.7
00058	25.2
00059	57.2
00060	8.4
00061	20.4
00062	31.9
00064	118.2
00065	68.3
RE 00067	49.6
00067	9.7
00068	25.0
00069	109.6
00072	4900.9
00073	8777.9
00074	6834.0
00075	75494.4
00076	171.8
00077	394.4
00078	74.5
00079	36.8
00082	45.8
00083	127.1
00084	93.4
00085	41.8
00089	39.6
00090	74.3
00091	59.6
00092	10.0
00094	168.5
00095	45.0
STANDARD DS2	205.0

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ___

SAMPLE#	Au* ppb
00101	260.8
00102	51.7
00103	259.9
00104	110.2
00105	70.8
00106	61.1
00107	174.7
00108	163.6
00109	47.7
00110	104.6
00111	58.3
00112	44.6
00113	173.1
00114	141.9
00116	63.5
00117	57.9
00118	128.3
00119	178.2
00120	13.7
RE 00120	6.7
00121	22.2
00122	23.0
00123	44.2
00124	215.0
00125	18.8
00126	5.5
00127	17.0
00128	24.9
00129	3.7
00130	26.0
00131	11.4
00132	10.2
00134	136.0
00135	665.2
STANDARD DS2	211.3

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Au* ppb
00136	55.0
00138	4016.5
00139	272.1
00140	167.0
00141	76.4
00142	77.2
00143	61.5
00144	18.4
00145	14.2
00146	116.9
00147	77.7
00148	32.7
00150	36.9
RE 00150	109.3
00151	22.8
00152	68.8
00153	97.2
00154	848.9
00155	609.9
00156	121.6
00157	16.4
00158	15.4
00160	10.6
00161	8.3
00162	28.7
00163	7.4
00164	12.8
00165	109.0
00166	6.4
00167	86.5
00170	193.4
00171	58.3
00172	75.2
00173	31.4
STANDARD DS2	203.1

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA

SAMPLE#	Au* ppb
00174	32.8
00175	167.0
00176	21.1
00177	75.9
00178	46.8
00179	37.6
00180	26.5
00181	47.0
00182	22.3
00183	35.8
00184	58.8
00185	91.9
RE 00186	651.7
00186	605.4
00187	947.0
00189	356.6
00190	57.9
00191	71.7
00192	89.9
00193	370.4
00195	13.4
00196	5.3
00198	24.0
00199	2.9
00200	7.1
00201	4.9
00202	7.3
00203	2.6
00204	136.6
00205	11.1
00206	28.0
00207	47.0
STANDARD DS2	202.4

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004326 Page 1

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00098	.5	43	22	84	.6	38	17	462	3.69	30	1	<2	6	12	.3	.9	<.5	28	.13	.069	25	27	.38	81	.006	2	1.42	.005	.09	1	1	2.0	<1	.01	4
00099	.4	32	17	64	.3	27	10	267	3.39	44	1	<2	3	13	.2	.7	1.1	26	.11	.081	23	21	.32	81	.005	4	1.12	.004	.07	1	<1	1.3	<1	.01	4
00100	.9	65	23	96	.9	49	25	966	3.88	34	3	<2	6	20	.4	<.5	.7	28	.16	.110	26	26	.36	108	.004	5	1.54	.006	.11	1	1	2.8	2	.02	4
00208	.3	20	19	53	<.1	19	7	178	3.98	30	1	<2	5	5	<.2	<.5	<.5	27	.06	.067	23	23	.29	54	.007	1	.94	.004	.07	2	1	1.4	<1	.01	3
00209	.4	18	14	41	.3	18	6	126	3.21	24	<1	<2	5	5	<.2	<.5	<.5	24	.05	.057	21	20	.26	43	.005	1	.81	.003	.05	1	<1	1.2	<1	.02	3
00210	.5	14	20	43	<.1	13	4	160	3.93	35	1	<2	4	8	.2	<.5	.7	31	.07	.092	22	21	.18	75	.010	4	.82	.004	.05	1	<1	.8	<1	.02	3
00211	.4	17	16	44	<.1	17	5	127	4.03	29	1	<2	5	3	.2	.9	<.5	33	.03	.087	22	32	.29	33	.006	2	1.01	.004	.04	1	<1	1.0	<1	.02	4
00212	.4	6	11	16	.1	9	1	41	2.44	22	<1	<2	4	4	<.2	<.5	.5	38	.02	.095	23	16	.09	34	.007	1	.77	.005	.03	1	<1	.6	<1	.02	5
00213	.4	9	16	27	.1	9	2	90	3.51	25	<1	<2	4	3	<.2	<.5	<.5	40	.03	.067	30	21	.16	47	.008	2	.98	.004	.04	1	<1	.8	<1	.01	5
00214	.7	18	56	52	.3	17	7	194	3.18	29	<1	<2	4	11	<.2	<.5	9.1	35	.16	.043	28	20	.27	54	.007	1	1.02	.004	.05	<1	<1	1.1	<1	.01	6
00215	.3	26	20	67	<.1	26	10	233	4.12	31	1	<2	5	5	.2	<.5	<.5	27	.04	.038	29	27	.44	75	.004	<1	1.38	.004	.05	<1	<1	1.6	<1	<.01	4
RE 00215	.3	26	20	65	<.1	27	10	231	4.17	32	1	<2	6	5	.2	.8	<.5	27	.04	.038	29	27	.44	75	.004	<1	1.37	.003	.05	1	<1	1.6	<1	.01	5
00216	.6	24	24	63	.1	23	10	254	3.42	24	1	<2	6	13	<.2	<.5	.5	29	.16	.048	27	22	.32	104	.004	1	1.42	.004	.06	<1	1	1.7	1	.01	5
00217	1.1	19	19	53	.2	18	6	174	3.34	21	1	<2	4	4	.2	<.5	.6	30	.05	.048	28	17	.17	34	.005	3	.97	.004	.05	<1	<1	.9	<1	.01	5
00218	.9	18	14	68	<.1	16	6	177	3.53	20	1	<2	3	10	<.2	<.5	.5	30	.15	.042	22	19	.20	53	.006	2	1.05	.004	.05	1	<1	.8	<1	.01	4
00219	1.4	25	24	67	<.1	24	8	299	5.26	41	1	<2	5	4	.2	<.5	<.5	35	.04	.058	29	25	.18	38	.020	<1	1.01	.004	.05	1	<1	1.1	<1	.02	5
00220	.9	19	27	55	<.1	19	6	192	4.86	26	1	<2	6	3	<.2	.6	1.0	29	.03	.071	19	22	.15	29	.016	<1	1.17	.004	.03	1	<1	.9	<1	.03	3
00221	.7	21	24	52	<.1	19	6	140	5.29	11	1	<2	7	2	<.2	.8	.8	33	.02	.064	30	21	.19	39	.009	<1	1.16	.004	.03	<1	<1	.9	<1	.02	6
00222	.3	6	4	29	<.1	12	1	69	3.15	12	1	<2	5	3	<.2	.5	<.5	29	.03	.064	13	14	.20	30	.006	<1	1.29	.004	.03	<1	<1	.6	<1	.03	6
00223	.4	6	4	27	<.1	10	1	66	2.92	12	1	<2	3	3	<.2	.7	<.5	29	.04	.066	13	14	.16	29	.005	1	1.21	.004	.03	<1	1	.6	<1	.03	6
00224	.4	9	3	23	<.1	9	1	46	2.38	10	<1	<2	4	3	<.2	<.5	<.5	29	.03	.057	13	12	.14	27	.004	<1	1.22	.004	.03	<1	<1	.6	<1	.02	6
00225	.6	20	18	60	<.1	19	5	128	4.87	21	1	<2	7	4	<.2	1.1	<.5	23	.02	.089	26	23	.36	32	.006	<1	1.56	.004	.05	<1	1	.8	<1	.03	6
00226	.3	12	10	31	<.1	11	3	61	3.27	30	<1	<2	4	3	.2	.7	<.5	32	.03	.042	26	14	.13	31	.007	<1	1.04	.003	.04	1	<1	.7	<1	.02	5
00227	.8	37	23	74	<.1	29	8	173	6.02	24	1	<2	12	4	<.2	1.0	.6	20	.04	.072	33	27	.33	57	.003	<1	1.76	.004	.07	1	1	1.2	<1	.03	6
00228	.8	10	7	31	<.1	5	1	85	2.31	5	<1	<2	9	5	<.2	<.5	.7	17	.05	.032	56	8	.14	73	.004	<1	.86	.003	.04	<1	<1	.5	<1	.01	6
00229	.3	22	8	43	.1	20	8	137	2.45	10	1	<2	6	17	<.2	.5	<.5	19	.22	.077	52	23	.29	80	.004	<1	1.65	.005	.04	2	<1	1.0	1	.03	6
00230	.4	20	20	45	.3	19	8	722	3.00	8	2	<2	4	9	<.2	<.5	<.5	21	.10	.079	35	21	.33	80	.006	<1	1.49	.004	.05	<1	1	1.5	3	.03	5
00231	1.1	24	34	73	.1	23	9	496	6.30	32	<1	<2	5	3	<.2	.8	<.5	30	.04	.082	29	23	.22	53	.010	<1	1.23	.004	.04	1	1	1.0	1	.03	5
00232	.9	14	17	60	<.1	13	5	185	5.28	25	<1	<2	5	4	<.2	1.0	<.5	35	.05	.061	31	20	.19	52	.012	1	1.22	.003	.04	<1	1	1.0	<1	.02	6
00233	.7	12	18	51	<.1	12	4	132	3.03	12	<1	<2	4	17	<.2	<.5	<.5	31	.20	.050	41	16	.20	76	.008	<1	1.26	.004	.04	<1	<1	1.0	2	.02	6
00234	1.3	33	36	85	<.1	28	11	346	6.98	44	<1	<2	9	4	<.2	1.1	<.5	34	.03	.077	30	24	.16	45	.022	2	.98	.003	.04	1	<1	1.6	<1	.02	6
00235	.4	10	15	26	<.1	9	2	82	1.96	14	<1	<2	2	4	<.2	<.5	<.5	22	.03	.069	29	11	.11	29	.004	1	.88	.003	.04	1	<1	.6	<1	.01	5
00236	.3	8	11	16	.1	6	2	44	1.99	7	<1	<2	2	3	<.2	<.5	<.5	18	.02	.029	25	8	.03	36	.009	1	.69	.004	.02	<1	<1	.4	<1	.02	4
00237	.5	12	9	22	<.1	9	3	64	1.69	10	<1	<2	3	3	<.2	<.5	<.5	19	.02	.036	36	7	.03	17	.007	<1	.52	.002	.03	<1	<1	.5	<1	.01	4
STANDARD C3	26.2	68	35	165	5.4	38	13	764	3.36	59	24	<2	21	30	22.4	13.0	23.2	83	.58	.098	18	180	.62	161	.086	23	1.84	.043	.19	16	2	4.1	3	.03	8
STANDARD G-2	1.6	2	3	44	<.1	8	4	538	2.05	1	3	<2	5	76	<.2	<.5	<.5	43	.66	.110	8	83	.62	238	.134	<1	.94	.088	.58	2	1	2.5	<1	<.01	5

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
- SAMPLE TYPE: SOIL SS80 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 25 2000 DATE REPORT MAILED: Nov 6/00 SIGNED BY: C. T. D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00238	.5	16	12	35	.1	9	3	81	2.27	14	<1	<2	6	4	<.2	<.5	<.5	19	.05	.036	34	9	.08	40	.004	1	.85	.005	.04	1	<1	.8	<1	.01	5
00239	<.2	12	16	76	<.1	25	7	123	4.23	10	1	<2	7	5	<.2	.5	<.5	23	.06	.043	24	23	.51	89	.004	2	1.61	.020	.04	<1	<1	1.2	<1	.02	8
00240	.5	16	28	79	.4	13	25	723	3.31	11	1	<2	3	26	<.2	.6	<.5	24	.32	.084	17	16	.17	100	.005	1	1.57	.008	.05	<1	1	1.4	<1	.03	5
00241	.7	13	12	46	.1	13	5	157	2.52	20	<1	<2	3	14	<.2	<.5	.5	26	.21	.027	26	12	.15	108	.008	<1	.69	.007	.07	<1	<1	1.0	<1	<.01	4
00242	.7	18	13	55	.2	17	8	360	2.75	19	1	<2	4	12	<.2	<.5	<.5	22	.19	.051	25	16	.30	72	.004	2	1.17	.006	.06	1	<1	1.7	1	.02	5
00243	.7	45	40	64	.4	40	15	539	4.95	14	1	<2	8	13	<.2	<.5	<.5	13	.25	.074	26	19	.23	57	.002	<1	1.05	.007	.04	<1	<1	1.5	<1	.04	4
00244	.6	25	51	105	.4	36	14	232	4.77	32	2	<2	5	15	<.2	<.5	.9	30	.26	.055	17	27	.26	67	.011	4	1.28	.010	.05	<1	<1	1.7	<1	.02	6
00245	.5	22	7	33	<.1	5	3	76	2.32	20	<1	<2	2	5	<.2	<.5	<.5	30	.08	.024	19	6	.05	46	.004	1	.59	.006	.03	<1	<1	1.6	1	<.01	4
00246	.4	22	26	61	<.1	21	8	188	4.00	36	1	<2	4	8	<.2	<.5	.5	28	.09	.035	26	18	.21	66	.005	2	.98	.005	.05	1	<1	1.5	<1	.01	4
00247	1.1	43	80	62	2.0	53	20	2227	3.25	41	6	<2	3	41	.4	<.5	1.1	18	.83	.167	16	19	.22	81	.006	<1	1.27	.010	.06	<1	<1	3.4	<1	.11	2
00248	.5	27	68	74	1.7	42	12	370	2.61	22	2	<2	3	26	.2	<.5	<.5	19	.41	.127	18	20	.38	82	.004	3	1.37	.006	.09	1	1	3.2	<1	.05	5
00249	.6	29	40	82	1.2	36	12	584	3.12	24	1	<2	4	21	.3	<.5	.5	22	.30	.109	21	21	.37	77	.005	<1	1.30	.006	.10	1	<1	2.9	<1	.03	4
00250	.5	35	22	63	.5	24	9	402	2.87	23	1	<2	1	22	.3	<.5	.5	26	.31	.075	21	19	.25	97	.007	<1	.98	.007	.10	1	1	1.3	<1	.02	5
RE 00250	.5	33	22	61	.5	24	9	394	2.81	23	1	<2	2	21	.3	<.5	<.5	26	.31	.075	21	19	.25	96	.007	2	.97	.008	.10	<1	<1	1.3	1	.02	4
00251	.3	16	14	49	.5	14	6	390	2.42	20	<1	<2	2	13	<.2	<.5	<.5	25	.19	.057	23	16	.21	71	.008	1	.87	.007	.08	<1	<1	1.1	1	.01	5
00252	.4	10	18	36	.3	10	3	151	2.60	26	<1	<2	1	5	.2	<.5	<.5	36	.06	.100	22	15	.16	49	.008	<1	.77	.005	.06	1	<1	.7	<1	.02	5
00253	.4	14	23	38	.2	12	4	125	3.11	25	<1	<2	6	4	<.2	<.5	<.5	22	.03	.042	26	16	.17	43	.006	1	.89	.004	.05	1	<1	1.1	<1	.01	4
00254	.4	12	21	33	.2	11	4	106	2.74	23	<1	<2	6	3	<.2	<.5	.6	19	.02	.042	26	14	.15	42	.006	2	.81	.005	.05	1	<1	1.0	<1	.01	4
00255	.4	14	21	38	.2	12	4	128	3.00	25	<1	<2	6	3	<.2	<.5	.5	22	.02	.043	28	16	.17	41	.006	1	.87	.004	.05	1	<1	1.2	<1	<.01	4
00256	.4	13	21	35	.3	12	4	119	2.84	24	<1	<2	5	4	<.2	<.5	<.5	22	.03	.047	25	15	.16	48	.006	2	.84	.015	.05	1	<1	1.1	<1	.02	4
00257	.4	12	19	35	.4	11	4	115	2.66	24	<1	<2	5	4	<.2	<.5	<.5	22	.03	.046	26	14	.15	47	.006	3	.76	.005	.05	1	<1	1.1	<1	.02	4
00302	.7	41	20	55	.3	28	12	327	3.32	28	2	<2	6	14	.3	<.5	<.5	30	.13	.074	32	21	.25	106	.004	<1	1.23	.007	.10	1	<1	3.2	<1	<.01	5
00303	2.1	49	40	93	1.3	57	20	770	4.60	333	2	5	4	22	2.1	1.0	8.3	29	.17	.089	29	20	.31	61	.004	3	1.03	.005	.09	1	<1	3.0	2	.02	4
00304	1.3	42	303	98	1.9	45	18	807	4.15	194	1	5	7	22	1.1	.7	8.0	25	.20	.084	28	20	.39	72	.004	2	1.07	.006	.10	1	<1	3.3	2	.03	4
00305	.8	36	21	84	.4	32	13	714	3.68	38	1	<2	1	28	.3	.9	1.3	28	.25	.108	19	19	.17	106	.007	4	.90	.006	.09	1	1	1.6	1	.02	4
00306	1.8	53	13	87	.2	45	17	292	4.45	26	1	<2	2	16	.2	1.7	1.5	28	.05	.129	22	11	.06	71	.006	1	.53	.012	.04	<1	<1	1.7	<1	.01	3
00307	1.6	23	11	45	.4	16	5	317	1.98	22	<1	<2	2	34	.2	.9	.9	32	.03	.054	20	10	.02	54	.006	<1	.28	.006	.03	<1	<1	.6	<1	.02	3
00308	.5	16	16	49	.4	14	5	126	4.08	28	1	<2	5	7	<.2	1.2	<.5	32	.04	.099	22	20	.21	39	.007	2	1.10	.005	.04	1	<1	1.4	1	.01	4
00309	.4	10	15	31	.1	9	3	94	2.81	24	<1	<2	3	5	<.2	<.5	<.5	28	.04	.139	23	15	.16	49	.005	3	.90	.006	.05	1	<1	1.0	<1	.02	4
00310	.6	20	18	65	.2	21	7	187	3.98	29	1	<2	6	7	.2	<.5	.8	29	.06	.068	25	25	.26	86	.009	3	1.24	.007	.06	1	<1	1.5	<1	.02	4
00311	.4	17	14	60	.4	18	7	213	3.47	28	<1	<2	3	7	.2	.7	<.5	30	.10	.076	25	21	.24	114	.010	3	1.07	.007	.10	1	<1	1.4	<1	.01	4
00312	.3	21	14	58	.2	25	9	228	3.45	25	1	<2	8	7	<.2	.9	<.5	35	.11	.051	25	26	.36	86	.025	<1	1.26	.006	.09	1	<1	2.1	<1	<.01	5
00313	.3	20	15	59	.1	20	8	269	3.09	21	<1	<2	2	7	<.2	<.5	<.5	36	.09	.048	21	27	.28	136	.010	4	1.40	.007	.12	1	<1	2.0	<1	.01	5
00314	.3	30	16	66	.2	33	13	458	3.44	22	1	<2	4	11	.2	.7	<.5	51	.23	.038	26	36	.47	149	.047	<1	1.64	.010	.11	<1	1	4.1	<1	<.01	5
STANDARD C3	26.6	66	35	163	5.4	37	12	754	3.24	58	24	<2	22	29	24.0	15.0	22.9	81	.58	.094	18	174	.61	156	.081	24	1.82	.045	.19	15	2	4.4	<1	.03	8
STANDARD G-2	1.6	2	3	44	<.1	8	4	515	1.99	1	4	<2	3	74	<.2	<.5	<.5	41	.63	.106	8	79	.60	235	.125	3	.90	.096	.56	2	1	2.7	1	<.01	6

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00315	.3	42	20	77	.1	33	11	378	4.01	24	1	<2	1	16	.2	.6	<.5	54	.21	.056	23	43	.43	237	.028	3	1.98	.010	.15	1	1	3.8	<1	.02	7
00316	.4	42	24	80	.3	40	17	894	3.93	28	1	<2	2	18	.3	<.5	<.5	41	.26	.073	25	39	.43	184	.018	4	1.85	.009	.15	1	1	4.0	<1	.02	5
00317	.2	54	21	111	<.1	51	24	538	4.25	22	1	<2	9	24	<.2	<.5	<.5	10	.38	.075	23	12	.29	42	.008	2	.74	.007	.06	<1	<1	2.6	1	<.01	3
00318	.4	48	26	86	<.1	40	19	700	3.90	40	<1	<2	10	40	.3	<.5	.7	21	.74	.071	33	17	.39	63	.014	4	.93	.009	.09	1	1	3.2	1	.01	4
00319	.5	46	25	84	<.1	40	19	717	3.70	37	1	<2	10	39	.2	<.5	<.5	19	.68	.075	32	16	.35	59	.016	2	.85	.008	.08	2	<1	3.0	<1	.01	3
00320	.4	41	23	75	<.1	37	17	755	3.56	31	1	<2	10	24	.2	<.5	.5	15	.35	.073	32	12	.24	41	.012	<1	.54	.007	.05	1	<1	2.3	<1	.02	2
00322	1.4	48	21	107	.1	50	17	508	3.47	19	5	<2	8	23	.4	<.5	<.5	35	.28	.065	24	27	.45	211	.050	3	1.29	.010	.07	<1	1	3.9	<1	<.01	5
00323	2.3	51	18	113	.2	50	16	512	3.31	11	4	<2	5	28	.4	.9	<.5	48	.29	.068	20	33	.52	256	.076	4	1.62	.011	.06	<1	1	4.9	1	<.01	5
00324	2.0	53	18	112	.1	55	19	645	3.84	19	2	<2	6	32	.3	.8	<.5	43	.40	.075	22	32	.60	231	.056	4	1.61	.012	.07	<1	1	4.7	<1	.01	5
00325	1.4	59	22	97	.2	56	24	1034	4.22	37	2	<2	7	37	.3	.5	1.1	26	.53	.081	23	21	.38	129	.020	2	1.05	.010	.06	<1	1	3.9	2	.01	4
00326	1.2	44	18	89	.1	42	15	550	3.39	19	2	<2	7	43	.2	<.5	<.5	37	.67	.064	22	26	.54	165	.050	4	1.31	.017	.09	<1	<1	4.0	<1	<.01	4
00327	1.8	50	18	131	.2	62	19	540	3.15	16	9	<2	15	21	.9	1.2	<.5	17	.15	.046	36	14	.22	191	.015	4	.75	.006	.06	<1	<1	2.7	<1	<.01	3
00328	1.2	45	20	93	.1	46	18	637	3.17	23	6	<2	9	29	.4	<.5	<.5	25	.40	.060	30	19	.37	157	.028	<1	.92	.010	.06	1	<1	3.0	1	<.01	4
00331	1.3	41	26	108	.2	71	19	1863	3.74	19	2	<2	5	26	.6	.9	<.5	42	.29	.081	20	29	.39	249	.092	2	1.06	.013	.06	<1	<1	4.6	<1	<.01	3
00332	1.0	48	20	90	.2	44	19	634	3.64	29	2	<2	8	23	.3	<.5	<.5	23	.24	.075	28	18	.28	119	.022	2	.85	.007	.07	1	<1	3.5	<1	.01	3
00333	.7	43	24	77	<.1	38	18	980	3.57	37	1	<2	9	20	.3	<.5	.5	23	.26	.070	32	15	.32	90	.013	2	.85	.008	.07	1	1	3.1	1	.01	3
00334	.4	22	23	66	.3	29	11	401	3.64	31	1	<2	1	11	<.2	<.5	<.5	34	.13	.096	23	31	.35	183	.008	2	1.59	.010	.17	1	<1	2.5	<1	.02	6
00335	.3	29	15	67	<.1	26	11	376	3.11	24	1	<2	3	7	<.2	<.5	<.5	28	.08	.054	27	26	.30	120	.009	4	1.48	.008	.13	1	1	2.5	<1	.01	5
RE 00335	.3	27	15	63	<.1	25	10	373	2.97	24	1	<2	2	7	<.2	<.5	.6	27	.08	.051	27	25	.30	114	.009	2	1.45	.007	.13	1	<1	2.4	<1	<.01	5
00337	.3	20	13	50	<.1	20	7	161	3.44	25	<1	<2	3	3	<.2	.5	<.5	21	.02	.051	27	20	.31	62	.004	<1	1.13	.006	.07	1	<1	1.4	<1	<.01	4
00338	.3	14	15	37	<.1	11	4	108	3.02	23	<1	<2	4	6	<.2	<.5	<.5	23	.03	.044	28	13	.17	54	.006	2	.83	.006	.05	1	<1	1.2	<1	<.01	4
00339	.3	11	13	30	.3	10	3	83	2.58	21	<1	2	4	7	<.2	<.5	<.5	19	.02	.051	23	14	.17	41	.004	4	.83	.005	.04	1	<1	.8	<1	.01	4
00340	.3	15	14	37	.1	10	5	228	2.69	20	<1	<2	3	4	<.2	<.5	<.5	22	.02	.048	28	15	.20	52	.005	4	1.05	.004	.05	1	<1	1.0	<1	<.01	5
00341	.4	13	11	28	.1	9	4	136	2.02	18	<1	<2	2	4	<.2	<.5	<.5	20	.02	.040	28	13	.14	48	.006	2	.91	.004	.04	1	<1	1.0	<1	<.01	5
00342	.4	23	16	72	<.1	21	8	211	3.46	25	1	<2	5	5	<.2	.9	<.5	25	.04	.067	25	22	.30	53	.008	5	1.39	.005	.05	1	<1	1.7	<1	.01	4
00343	.5	27	15	75	.4	23	9	222	4.16	30	<1	<2	6	5	.2	<.5	<.5	28	.06	.101	27	22	.34	49	.009	2	1.30	.005	.05	4	<1	2.0	<1	.01	3
00344	.6	27	15	79	.2	30	10	224	4.32	26	1	<2	5	7	.2	1.1	<.5	38	.13	.092	22	29	.34	74	.022	<1	1.49	.006	.05	1	1	2.3	<1	.02	4
00345	.4	17	14	48	<.1	14	7	346	2.65	24	<1	<2	4	7	<.2	<.5	<.5	26	.04	.083	28	17	.20	61	.009	4	.96	.005	.05	1	<1	1.9	<1	<.01	5
00346	.3	27	17	56	.2	18	9	400	2.29	23	1	<2	<1	13	.2	<.5	<.5	21	.12	.057	26	15	.18	75	.007	3	.82	.005	.07	1	<1	1.4	<1	<.01	4
00347	.4	28	22	65	.1	22	8	225	3.23	35	1	<2	1	15	.3	<.5	.6	23	.13	.064	24	19	.22	77	.006	2	.98	.006	.08	1	<1	1.4	<1	.01	4
00348	1.0	41	37	91	.3	37	15	546	3.80	56	1	<2	4	14	.4	<.5	.6	27	.14	.056	27	21	.29	77	.007	5	1.12	.005	.08	1	<1	2.5	<1	.01	3
00349	.2	25	21	75	<.1	25	9	268	3.41	34	<1	<2	3	12	<.2	<.5	.5	22	.15	.060	25	20	.30	73	.006	4	.97	.006	.07	1	<1	1.6	<1	<.01	4
00350	.4	38	21	81	.1	47	19	819	3.43	32	1	<2	6	12	.4	<.5	<.5	25	.16	.056	30	22	.39	79	.011	<1	1.08	.007	.07	1	<1	2.8	<1	.01	4
00352	.4	26	17	65	.2	27	11	369	2.97	31	1	<2	3	15	.3	<.5	<.5	24	.19	.060	26	18	.29	74	.009	3	.92	.007	.07	1	<1	1.9	<1	.01	3
STANDARD C3	25.9	66	34	169	5.3	36	12	769	3.31	58	23	<2	20	30	24.0	16.0	22.3	81	.59	.093	18	174	.62	156	.091	20	1.86	.047	.17	17	2	4.4	<1	.02	8
STANDARD G-2	1.6	2	2	44	<.1	7	4	523	2.03	<1	2	<2	3	71	<.2	<.5	<.5	41	.65	.103	7	80	.60	232	.130	1	.91	.082	.50	2	1	2.6	2	<.01	6

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00353	.7	79	37	124	1.0	60	22	1480	4.54	38	3	<2	5	27	.8	1.0	.6	31	.36	.126	26	36	.45	160	.008	2	1.94	.010	.16	1	<1	5.2	<1	.03	6
00354	1.0	57	37	114	1.1	60	24	1035	4.42	36	3	<2	8	27	.5	.5	1.0	32	.31	.100	30	33	.43	156	.006	<1	1.99	.008	.15	1	1	5.6	<1	.02	5
00355	.3	36	21	85	.4	35	15	648	3.44	26	2	<2	3	22	.3	<.5	.5	25	.31	.073	23	25	.40	103	.005	1	1.34	.005	.08	1	1	2.4	<1	.02	4
00356	<.2	35	22	72	.3	33	13	451	3.33	30	1	<2	6	9	.2	.7	<.5	20	.09	.040	31	19	.34	68	.004	<1	1.09	.004	.07	1	<1	2.3	<1	<.01	3
00358	<.2	27	16	62	<.1	24	8	215	3.18	30	<1	<2	7	3	<.2	<.5	<.5	23	.03	.041	28	20	.31	62	.006	<1	.95	.004	.07	1	<1	1.7	<1	<.01	4
00359	<.2	23	14	63	<.1	23	9	204	3.77	28	<1	<2	5	4	.2	<.5	<.5	22	.04	.044	29	22	.34	62	.005	<1	1.18	.003	.07	1	<1	1.7	<1	<.01	4
00360	.3	3	5	8	<.1	2	1	98	.62	6	<1	<2	2	3	<.2	<.5	<.5	12	.02	.025	31	5	.04	48	.005	<1	.46	.003	.03	<1	<1	.3	1	<.01	4
00361	.2	21	17	59	.1	18	7	173	3.85	25	1	<2	6	5	<.2	<.5	<.5	24	.03	.050	23	23	.26	46	.007	2	1.21	.003	.04	1	<1	1.5	<1	.01	4
00362	.2	18	12	59	<.1	18	7	173	3.59	24	<1	<2	6	3	<.2	<.5	<.5	23	.03	.049	22	22	.27	38	.006	<1	1.19	.003	.04	1	<1	1.3	<1	.01	4
00363	.3	21	14	51	<.1	18	7	159	3.81	22	1	<2	6	3	<.2	<.5	<.5	23	.02	.038	26	21	.30	41	.006	<1	1.14	.003	.04	1	<1	1.3	<1	.01	4
00364	.2	23	14	56	<.1	25	11	321	3.27	22	1	<2	6	9	<.2	<.5	<.5	25	.10	.038	23	22	.46	43	.004	<1	1.33	.003	.04	1	<1	1.9	<1	<.01	5
00365	.6	29	23	66	<.1	25	13	393	3.87	21	1	<2	7	13	<.2	.7	.6	34	.16	.036	23	23	.35	83	.006	<1	1.53	.005	.07	1	1	2.5	<1	.01	5
RE 00365	.6	29	24	64	<.1	26	13	394	3.96	22	1	<2	6	13	.2	.7	<.5	34	.16	.037	24	24	.35	86	.006	<1	1.52	.004	.07	1	<1	2.6	<1	<.01	6
00366	.5	27	26	86	.1	31	17	542	3.37	22	1	<2	4	14	.2	<.5	<.5	22	.20	.073	22	21	.41	61	.005	<1	1.29	.004	.07	1	<1	1.8	<1	.02	4
00367	.5	14	12	43	<.1	12	4	110	2.44	20	<1	<2	1	13	<.2	<.5	.5	30	.19	.033	25	11	.12	57	.008	<1	.65	.003	.04	1	<1	.7	<1	.01	4
00368	.5	26	33	73	.1	25	12	768	2.98	22	2	<2	2	24	.3	<.5	<.5	26	.35	.064	19	18	.22	68	.008	<1	.97	.005	.07	<1	1	2.0	<1	.02	3
00369	1.3	36	33	84	.4	30	13	350	4.81	35	2	<2	3	23	.5	<.5	.5	25	.31	.059	19	21	.21	63	.008	1	1.05	.005	.06	2	1	1.7	<1	.02	4
00370	2.7	32	29	47	<.1	17	7	151	3.09	49	<1	<2	6	3	.2	<.5	1.8	20	.03	.037	27	9	.07	26	.007	<1	.48	.002	.04	1	<1	.7	<1	<.01	3
00371	.3	18	18	42	<.1	15	6	263	3.84	56	<1	<2	5	4	.3	<.5	.8	23	.04	.053	26	12	.04	46	.008	<1	.56	.003	.04	1	<1	.9	<1	.01	3
00372	1.1	24	14	36	.1	15	5	189	2.24	33	<1	<2	4	4	<.2	<.5	.9	30	.04	.039	33	8	.03	36	.008	1	.44	.003	.03	1	<1	.8	<1	<.01	3
00373	.3	28	40	66	.6	34	19	958	3.64	45	2	<2	3	17	.4	<.5	.7	20	.29	.065	21	18	.22	68	.008	<1	1.03	.004	.06	2	<1	2.5	1	.02	2
00374	.6	41	45	87	.8	48	16	2457	3.79	31	6	<2	3	31	.6	<.5	1.0	25	.69	.178	17	26	.27	125	.009	3	1.78	.008	.11	1	<1	4.1	<1	.07	3
00375	.7	13	18	71	.2	15	6	229	2.82	16	1	<2	3	16	<.2	<.5	<.5	32	.22	.039	21	20	.25	81	.011	<1	1.29	.005	.06	<1	<1	1.6	<1	.02	6
00376	.6	12	9	28	<.1	9	3	42	1.12	10	<1	<2	2	8	<.2	<.5	<.5	21	.11	.021	26	9	.03	59	.004	<1	.59	.004	.04	1	<1	.5	<1	<.01	5
00377	.4	19	14	44	<.1	16	6	162	2.44	30	<1	<2	3	3	.2	<.5	.5	21	.03	.038	29	9	.06	32	.005	<1	.62	.004	.04	1	<1	.9	<1	<.01	3
00378	.3	14	22	63	.1	19	6	139	2.98	17	<1	<2	4	8	<.2	<.5	.8	26	.09	.046	24	13	.12	61	.006	<1	.87	.005	.05	<1	<1	.8	<1	.02	5
00379	.3	17	6	48	<.1	17	6	142	2.91	43	<1	<2	3	4	.2	.5	.5	19	.04	.053	33	7	.03	22	.004	<1	.54	.004	.02	2	<1	1.1	<1	.01	3
00380	.3	7	10	16	<.1	6	1	37	1.08	11	<1	<2	4	2	<.2	<.5	<.5	12	.01	.028	38	4	.02	31	.003	<1	.68	.004	.02	<1	<1	.4	1	<.01	4
00381	.4	20	23	50	<.1	16	5	164	4.26	24	<1	<2	6	6	<.2	<.5	1.3	29	.06	.040	26	13	.07	45	.008	<1	.90	.004	.05	1	<1	.9	<1	.02	3
00382	.6	13	18	45	<.1	17	5	101	4.90	17	1	<2	10	3	<.2	.5	.5	31	.02	.067	22	24	.24	44	.005	1	1.61	.003	.03	1	<1	1.1	1	.02	6
00383	.5	17	27	48	1.6	15	5	187	3.99	6	1	9	10	3	<.2	<.5	.9	22	.03	.051	31	18	.20	33	.004	2	1.27	.003	.03	<1	<1	.8	<1	.02	5
00384	.8	23	22	44	<.1	18	5	123	2.87	18	1	<2	6	4	<.2	.7	<.5	21	.03	.059	26	17	.23	49	.004	1	1.47	.004	.06	<1	<1	1.1	<1	.03	5
00385	1.3	17	57	60	<.1	18	9	469	5.01	26	1	<2	5	14	.3	<.5	1.2	35	.15	.061	24	22	.15	106	.007	<1	1.47	.005	.07	1	<1	1.4	<1	.02	6
00386	.3	15	25	40	<.1	13	4	93	2.96	27	1	<2	6	5	.2	<.5	.5	14	.05	.056	27	13	.14	48	.002	<1	1.05	.004	.05	<1	<1	.7	<1	.02	4
STANDARD C3	26.1	65	35	168	5.2	36	11	741	3.23	58	23	<2	20	28	23.2	14.3	22.3	78	.57	.089	17	168	.60	150	.085	22	1.79	.043	.17	16	2	4.3	<1	.02	7
STANDARD G-2	1.4	2	2	46	<.1	7	4	500	1.92	1	2	<2	4	71	<.2	<.5	<.5	41	.62	.099	7	76	.58	220	.125	<1	.88	.083	.48	2	<1	2.5	<1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00387	.9	36	37	83	.3	37	13	623	4.65	30	2	<2	1	16	.2	<.5	1.0	31	.23	.088	22	29	.28	104	.012	2	1.90	.009	.09	1	<1	1.8	<1	.04	5
00388	.9	29	15	62	<.1	32	11	326	4.99	26	<1	<2	7	12	<.2	<.5	1.3	34	.13	.069	55	29	.29	98	.004	<1	1.27	.007	.06	<1	<1	1.1	<1	.02	7
00389	1.7	23	22	74	.2	19	7	146	4.84	27	1	<2	7	5	.3	<.5	1.0	40	.05	.038	28	21	.14	57	.009	1	1.39	.006	.06	1	<1	1.7	<1	.02	4
00390	.7	13	9	36	<.1	11	4	108	2.21	26	<1	<2	4	2	<.2	<.5	1.3	36	.03	.026	39	8	.04	25	.012	1	.61	.003	.03	1	<1	.9	<1	<.01	5
00391	.5	19	26	44	.1	16	5	139	4.60	25	<1	<2	3	3	<.2	<.5	1.2	34	.03	.061	25	25	.13	40	.010	<1	1.04	.006	.05	1	<1	1.3	<1	.02	4
00392	.3	11	13	31	.1	11	3	97	3.63	20	<1	<2	4	3	<.2	<.5	1.2	38	.04	.064	21	18	.12	36	.010	1	1.08	.005	.04	<1	<1	1.1	<1	.02	4
00393	.3	12	13	40	.1	11	3	83	3.39	18	<1	<2	4	4	<.2	<.5	.5	26	.02	.063	23	15	.15	38	.004	<1	1.15	.007	.04	<1	<1	1.2	<1	.03	4
00394	1.1	42	11	59	.1	33	10	102	5.09	155	<1	<2	7	6	.6	<.5	1.3	23	.02	.084	33	8	.02	21	.010	<1	.30	.005	.05	1	<1	.8	<1	.01	3
00395	.5	20	31	43	.4	16	7	238	3.64	20	<1	<2	2	6	<.2	<.5	1.0	19	.03	.050	25	11	.06	37	.005	1	.85	.005	.03	<1	<1	.8	<1	.02	2
00396	.6	21	30	54	.2	19	7	240	3.89	23	1	<2	1	5	<.2	1.0	1.5	27	.03	.048	29	11	.05	40	.006	<1	.85	.007	.03	1	<1	1.0	<1	.02	3
00397	.2	24	22	48	.2	23	7	181	3.13	37	<1	<2	1	5	.2	<.5	<.5	19	.05	.045	26	17	.22	58	.007	<1	.91	.005	.06	1	<1	1.2	<1	.01	2
00398	.2	30	32	56	.1	27	9	221	3.61	39	1	<2	2	6	.2	<.5	.9	21	.07	.052	26	22	.26	75	.011	1	1.28	.006	.06	1	<1	1.6	<1	.02	3
00400	<.2	21	19	57	.2	22	9	337	3.71	21	1	<2	4	3	<.2	.5	.7	25	.04	.068	30	21	.37	69	.004	1	1.22	.005	.06	<1	<1	1.7	<1	.02	4
RE 00400	<.2	20	18	52	.1	20	8	309	3.53	21	<1	<2	4	3	<.2	<.5	<.5	23	.03	.064	26	20	.35	65	.004	<1	1.14	.005	.05	<1	<1	1.6	<1	.02	3
00401	.4	15	19	41	1.1	12	4	113	3.67	21	<1	<2	6	4	<.2	.5	.6	27	.06	.072	29	18	.19	41	.008	<1	.96	.005	.05	<1	<1	1.4	<1	.01	4
00402	.4	22	17	62	.1	23	9	209	4.34	26	<1	<2	6	9	<.2	<.5	<.5	27	.15	.053	28	24	.42	49	.007	<1	1.21	.006	.05	<1	<1	1.7	<1	.01	4
00403	.5	21	20	64	.1	23	8	172	4.07	29	<1	<2	1	8	<.2	<.5	.6	27	.09	.177	22	22	.30	66	.007	<1	1.01	.007	.06	1	<1	1.4	<1	.01	2
00404	.6	26	22	67	.2	26	10	243	5.19	28	<1	<2	5	4	.2	<.5	<.5	26	.03	.052	25	23	.30	61	.006	1	1.22	.006	.05	1	<1	1.8	<1	.01	5
00406	.7	52	29	104	.5	50	20	619	4.58	34	2	<2	5	17	.5	.5	.5	25	.21	.099	24	27	.39	120	.004	1	1.58	.015	.11	1	<1	3.1	1	.02	4
00407	.9	49	23	108	.6	43	23	624	4.37	31	2	<2	4	22	.3	<.5	.6	26	.26	.101	27	25	.35	84	.005	<1	1.35	.009	.09	1	<1	2.7	<1	.02	4
00408	.8	44	154	102	.7	43	18	723	4.20	23	3	<2	6	17	.4	<.5	.5	27	.15	.133	32	26	.38	112	.004	<1	1.62	.012	.10	1	1	4.3	1	.02	5
00409	.8	35	49	74	.5	30	15	2263	3.49	23	2	<2	1	30	.3	<.5	<.5	30	.37	.127	22	20	.18	112	.006	<1	1.02	.008	.08	<1	<1	1.8	1	.03	3
00412	1.9	22	36	57	.5	20	7	165	6.04	62	<1	<2	3	15	.3	<.5	.9	63	.10	.211	25	25	.21	74	.018	<1	.94	.005	.06	2	<1	1.8	<1	.02	6
00413	.5	18	18	55	.2	19	7	168	4.07	21	<1	<2	3	11	.2	<.5	.5	29	.10	.128	24	22	.35	59	.005	2	1.05	.005	.04	1	<1	1.5	<1	.02	3
00414	.4	37	24	85	.9	44	15	730	3.79	32	1	<2	1	23	.4	<.5	.7	30	.29	.099	25	25	.39	108	.007	2	1.36	.007	.11	2	1	3.3	<1	.02	3
00415	<.2	27	16	68	<.1	28	11	330	3.32	25	<1	<2	4	4	.2	<.5	<.5	25	.05	.045	32	23	.41	59	.009	2	1.04	.005	.06	1	<1	2.2	<1	<.01	3
00416	.4	25	17	70	.4	29	10	287	3.49	23	<1	<2	4	7	.3	<.5	.5	37	.15	.060	23	27	.37	83	.030	<1	1.46	.007	.07	1	1	2.2	<1	.01	3
00417	.4	16	11	66	.3	18	9	300	3.02	16	<1	<2	1	6	.2	<.5	<.5	35	.11	.060	22	23	.28	70	.020	<1	1.42	.006	.05	1	<1	1.7	<1	.01	3
00418	.3	13	13	44	.2	13	5	188	3.44	17	<1	<2	1	4	<.2	<.5	<.5	31	.05	.050	24	21	.25	67	.009	4	1.18	.006	.06	1	<1	1.3	<1	.01	4
00419	.4	28	17	82	.2	31	12	302	4.18	25	<1	<2	5	5	.2	.6	<.5	31	.06	.057	26	28	.37	78	.012	<1	1.65	.006	.08	1	<1	2.3	<1	.02	4
00420	.5	23	22	71	.3	26	9	299	4.35	24	<1	<2	4	8	.2	<.5	<.5	35	.07	.076	27	29	.35	104	.011	<1	1.55	.007	.11	1	<1	2.1	1	.01	4
00421	.5	30	23	78	.3	30	12	328	4.03	27	<1	<2	5	5	.2	<.5	.6	25	.05	.069	32	24	.39	77	.007	<1	1.44	.004	.09	1	<1	2.1	<1	.01	3
00422	.3	27	19	143	.3	38	11	569	2.11	15	1	<2	<1	23	.4	<.5	<.5	22	.34	.070	23	12	.28	76	.006	1	.77	.008	.08	1	<1	1.4	2	.03	3
00423	.4	47	26	89	.3	40	19	873	4.00	39	<1	<2	12	56	.3	<.5	<.5	27	1.09	.065	31	20	.52	90	.010	<1	1.16	.011	.15	1	<1	4.0	2	.02	3
STANDARD C3	27.9	68	37	174	5.7	39	13	800	3.50	60	24	<2	23	31	25.7	16.0	24.0	87	.62	.100	19	179	.65	165	.092	24	1.86	.047	.18	16	2	4.8	1	.03	8
STANDARD G-2	1.5	2	2	45	<.1	8	4	522	2.00	<1	2	<2	3	72	<.2	<.5	<.5	42	.64	.106	8	79	.60	237	.128	3	.87	.086	.50	2	1	2.6	1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00424	1.1	53	30	100	.1	52	23	853	4.45	40	2	<2	10	29	.6	.9	.7	28	.25	.084	32	19	.31	102	.015	<1	1.00	.006	.08	<1	1	4.1	<1	.01	2
00425	.7	49	26	91	.1	45	20	820	4.01	38	1	<2	10	36	.6	.6	<.5	24	.21	.080	34	17	.33	75	.012	<1	.90	.005	.08	1	<1	3.5	<1	.02	2
00426	.6	44	26	91	.1	43	20	769	3.72	40	1	<2	8	21	.5	<.5	<.5	22	.30	.072	30	17	.36	69	.012	<1	.82	.006	.08	1	1	3.3	<1	.01	3
00428	4.3	89	15	235	.4	100	19	446	4.43	20	15	<2	5	21	.9	2.5	<.5	34	.11	.073	20	26	.45	480	.031	<1	.98	.005	.04	<1	<1	3.3	<1	.01	2
00429	3.1	115	15	288	.2	133	30	1269	4.51	14	17	<2	10	19	1.6	2.3	.5	22	.10	.061	26	19	.30	452	.020	3	.76	.004	.04	<1	<1	3.0	1	.02	1
00433	1.1	45	14	110	.2	50	12	178	2.58	2	6	<2	5	38	.4	.6	<.5	52	.40	.054	19	38	.67	433	.085	<1	1.78	.017	.08	<1	<1	5.5	<1	<.01	5
00434	2.0	56	18	119	.3	56	17	536	3.60	17	6	<2	8	36	.6	1.0	<.5	38	.40	.068	24	28	.57	433	.049	1	1.48	.011	.08	<1	<1	4.3	<1	<.01	3
00435	2.0	58	19	124	.3	58	18	535	3.78	20	6	<2	8	39	.5	1.0	<.5	36	.47	.071	25	27	.55	407	.043	<1	1.42	.011	.08	1	<1	4.0	<1	<.01	3
00436	3.4	62	18	165	.3	80	19	587	4.17	20	10	<2	8	25	.7	1.8	<.5	34	.28	.072	26	26	.46	362	.042	2	1.20	.010	.06	<1	<1	3.5	1	<.01	3
00438	1.4	126	34	163	.5	129	79	2424	4.12	27	5	<2	11	12	2.5	1.0	.8	20	.14	.110	31	17	.28	193	.012	<1	1.41	.005	.07	1	<1	4.9	<1	<.01	1
00439	2.8	84	28	249	.2	137	43	637	6.32	55	4	<2	8	20	1.8	2.0	1.3	26	.10	.127	23	29	.22	78	.016	1	.84	.004	.05	1	<1	5.0	<1	<.01	2
00440	.5	43	27	81	.1	41	19	861	3.74	32	1	<2	10	35	.4	.6	.7	29	.57	.069	32	23	.45	85	.019	1	1.09	.007	.09	1	1	3.8	2	<.01	3
00441	.3	44	21	79	.1	42	19	695	3.78	26	1	<2	10	66	.3	<.5	<.5	32	1.33	.074	31	29	.65	106	.022	<1	1.33	.009	.12	<1	<1	4.1	<1	<.01	4
00442	.3	42	36	89	<.1	40	18	747	3.67	31	1	<2	7	15	.5	1.2	<.5	32	.14	.058	35	25	.43	110	.017	1	1.30	.006	.11	1	1	4.1	1	<.01	3
00443	.4	25	47	80	.2	26	13	622	3.15	28	1	<2	1	13	.3	.9	.7	23	.11	.075	24	20	.32	74	.007	<1	1.08	.004	.08	1	<1	1.8	1	.01	3
00444	.5	26	47	71	.3	25	11	532	2.89	29	<1	<2	4	14	.4	.8	.7	22	.15	.058	26	17	.29	61	.007	1	.94	.004	.06	2	<1	1.9	1	.01	2
00445	1.0	19	17	60	.1	16	5	150	3.39	23	<1	<2	1	15	.2	1.0	<.5	26	.04	.087	23	16	.17	55	.007	<1	.80	.003	.05	1	<1	1.1	<1	.01	2
RE 00445	1.0	18	17	59	.1	16	5	151	3.28	23	<1	<2	<1	15	.2	.9	.9	27	.04	.092	23	16	.17	58	.007	<1	.80	.003	.05	1	<1	1.1	<1	.01	3
00446	.9	27	21	67	.1	22	6	194	2.78	27	<1	<2	2	21	.3	1.3	<.5	21	.04	.071	23	14	.17	59	.006	<1	.74	.004	.06	1	<1	1.1	<1	.02	3
00447	.8	24	20	66	.1	21	6	208	4.14	31	<1	<2	4	17	.3	.7	<.5	25	.05	.094	24	21	.22	58	.005	<1	.96	.004	.06	1	<1	1.6	<1	.02	2
00448	.6	20	16	61	.1	16	6	168	2.62	26	<1	<2	5	13	.2	1.1	.6	22	.04	.059	29	16	.14	51	.007	<1	.91	.003	.05	1	<1	1.5	<1	.01	2
00449	.4	15	20	40	.1	14	5	200	2.63	24	<1	<2	1	7	.2	1.1	<.5	23	.04	.113	23	15	.22	46	.005	<1	.88	.003	.05	1	<1	1.0	<1	.01	3
00450	.6	33	27	71	.2	29	13	571	3.12	26	1	<2	2	12	.4	1.1	.5	23	.09	.081	26	19	.26	59	.007	<1	1.15	.004	.06	1	<1	1.8	<1	.01	2
00451	.7	47	30	103	.6	44	26	1166	3.78	31	4	<2	2	34	.6	1.3	.8	21	.31	.139	20	22	.27	84	.008	1	1.23	.006	.10	1	<1	2.9	<1	.03	2
00452	.9	27	30	66	<.1	25	8	238	4.19	42	<1	<2	1	15	.3	.9	.7	34	.08	.180	21	18	.10	62	.013	<1	.63	.004	.04	1	<1	1.1	<1	.02	3
00453	.6	49	33	78	.7	40	27	841	3.77	30	2	<2	2	28	.6	.5	.9	27	.35	.096	24	22	.19	95	.007	1	1.26	.006	.11	1	1	2.6	1	.02	3
00454	.5	12	18	31	<.1	9	2	69	2.37	23	<1	<2	2	8	<.2	<.5	<.5	21	.03	.062	23	11	.07	33	.007	1	.55	.003	.04	1	<1	.8	<1	.01	3
00455	.5	18	17	54	.2	19	7	297	3.21	35	<1	<2	1	14	.2	<.5	.6	24	.17	.069	25	16	.18	54	.008	<1	.69	.004	.06	1	<1	1.2	<1	.01	2
00456	.4	34	26	77	.5	38	15	523	3.51	46	1	<2	3	12	.4	1.2	.8	25	.13	.052	32	22	.29	74	.007	2	1.13	.005	.09	1	<1	2.8	<1	.01	3
00457	.6	49	39	82	.3	38	18	1028	3.68	37	2	<2	4	16	.5	1.6	1.1	26	.19	.068	33	25	.27	89	.008	<1	1.31	.005	.11	1	<1	3.1	1	.02	3
00458	.4	29	25	62	.3	30	13	512	3.52	29	1	<2	4	10	.2	.6	.7	23	.15	.056	30	21	.39	57	.006	<1	1.26	.005	.08	1	<1	2.2	<1	.01	3
00460	.4	19	19	54	<.1	17	6	173	3.46	24	<1	<2	3	6	.2	.6	<.5	28	.10	.056	24	15	.15	53	.009	<1	.81	.004	.05	1	<1	1.1	<1	.01	4
00461	.6	17	20	59	<.1	16	6	150	3.94	25	<1	<2	3	6	.2	.7	.9	28	.09	.044	24	18	.22	70	.008	<1	1.02	.003	.05	1	<1	1.1	<1	.01	4
00462	.5	16	19	80	<.1	19	8	187	3.82	23	<1	<2	4	11	<.2	.5	<.5	25	.21	.037	21	21	.34	57	.007	<1	1.20	.004	.05	1	<1	1.5	<1	.01	3
STANDARD C3	26.4	66	35	170	5.3	38	12	748	3.26	58	23	<2	20	30	24.8	14.9	22.8	80	.58	.095	18	181	.60	159	.088	21	1.83	.044	.17	16	2	4.4	2	.03	8
STANDARD G-2	1.5	2	3	46	<.1	8	4	545	2.09	<1	2	<2	5	78	<.2	<.5	<.5	42	.69	.105	9	84	.63	237	.137	3	.96	.090	.53	2	1	2.8	1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data /- FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00463	.6	22	15	52	.1	16	6	173	3.51	24	<1	<2	1	8	.2	<.5	.8	30	.12	.034	26	17	.25	81	.009	3	.91	.005	.05	1	<1	1.1	<1	.01	5
00464	.6	29	25	69	.2	27	11	340	4.48	30	1	<2	4	14	.3	<.5	<.5	32	.23	.057	22	23	.43	57	.006	4	1.40	.006	.07	1	<1	1.7	<1	.02	5
00465	1.8	12	12	31	<.1	14	4	107	1.75	48	<1	<2	1	12	.2	<.5	<.5	23	.18	.028	28	8	.08	39	.006	<1	.53	.005	.03	1	<1	.8	<1	<.01	5
00466	.5	15	25	41	.1	12	4	110	3.46	29	<1	<2	3	7	.2	<.5	1.0	26	.09	.036	23	13	.13	48	.007	2	.78	.004	.04	1	<1	.9	<1	.01	3
00467	.2	55	22	76	.1	47	22	710	4.19	32	1	<2	13	11	.2	.5	<.5	26	.14	.057	39	22	.58	46	.006	<1	1.39	.007	.10	1	1	3.2	<1	<.01	4
00469	.4	12	8	20	.1	7	2	63	1.32	14	<1	<2	1	5	<.2	<.5	<.5	15	.06	.024	30	9	.10	58	.004	<1	.63	.005	.05	<1	<1	.7	<1	<.01	4
00470	.3	28	20	63	.4	25	12	706	3.12	26	1	<2	4	14	.2	<.5	<.5	22	.25	.060	24	18	.28	94	.004	<1	1.21	.007	.10	1	<1	2.1	<1	.02	3
00471	.3	38	32	73	.5	36	15	632	3.50	29	2	<2	4	19	.3	<.5	.5	21	.36	.072	25	20	.35	71	.005	2	1.30	.007	.11	1	1	3.1	<1	.02	3
00472	.3	34	22	68	.3	34	16	589	3.32	32	1	<2	6	14	.2	<.5	<.5	19	.25	.054	33	20	.39	50	.008	3	1.07	.007	.08	3	1	2.6	<1	.01	3
00473	.2	34	21	76	.3	33	15	594	3.36	31	2	<2	5	12	.2	<.5	<.5	21	.23	.042	33	21	.40	53	.007	3	1.15	.006	.07	1	1	2.7	<1	.01	3
00474	.4	58	26	75	.6	41	16	944	3.72	33	3	<2	3	24	.4	.6	<.5	25	.49	.099	24	25	.36	87	.008	2	1.48	.007	.11	1	1	3.5	<1	.04	3
00475	.7	87	29	83	1.3	50	17	542	4.65	37	5	<2	5	31	.4	.5	<.5	32	.54	.095	35	29	.34	117	.006	<1	2.03	.009	.13	1	1	4.7	<1	.03	6
RE 00475	.6	86	28	81	1.3	49	16	534	4.59	35	5	<2	5	31	.4	<.5	.5	30	.53	.095	34	29	.33	116	.006	1	2.01	.010	.13	1	1	4.7	<1	.03	5
00476	.3	27	18	55	.1	24	9	245	3.05	28	1	<2	6	4	<.2	.6	<.5	19	.06	.036	27	20	.33	46	.005	<1	1.10	.005	.06	1	<1	1.6	<1	.01	3
00477	.3	35	24	62	.4	32	15	591	3.77	27	2	<2	6	13	.3	1.5	<.5	25	.17	.056	27	23	.41	59	.005	<1	1.60	.006	.07	1	1	2.3	<1	.02	4
00478	.5	25	22	81	.1	21	11	580	3.44	24	2	<2	2	21	<.2	<.5	<.5	27	.25	.055	29	19	.26	69	.008	<1	1.18	.006	.06	1	<1	1.5	<1	.02	4
00479	.6	12	8	29	<.1	10	3	85	1.94	23	<1	<2	3	6	<.2	.5	.8	27	.09	.025	28	8	.07	49	.006	<1	.61	.004	.05	1	<1	.8	<1	<.01	4
00480	.4	11	9	40	<.1	10	4	85	2.44	18	<1	<2	5	6	<.2	<.5	<.5	19	.06	.027	33	10	.12	55	.005	1	.75	.005	.04	1	<1	.7	<1	<.01	5
00481	.6	15	22	54	<.1	16	5	118	4.28	12	1	<2	6	6	<.2	.9	<.5	23	.07	.051	28	16	.22	71	.005	2	1.16	.005	.04	<1	<1	1.0	<1	.02	5
00482	.7	14	13	64	.1	15	7	237	2.96	17	1	<2	6	31	<.2	<.5	.5	23	.34	.031	36	17	.22	89	.003	<1	1.22	.004	.06	1	<1	1.4	<1	<.01	5
00483	.7	17	16	51	.1	18	5	123	3.60	24	1	<2	5	5	<.2	.7	<.5	19	.06	.044	36	16	.15	42	.004	<1	.88	.005	.05	1	<1	1.0	<1	.02	3
00484	.9	29	35	54	.1	18	6	159	5.81	20	1	<2	8	5	<.2	1.4	1.1	24	.04	.076	27	18	.17	49	.004	<1	1.16	.006	.07	1	<1	1.1	<1	.02	5
00485	.4	13	13	35	.1	11	3	88	2.59	22	<1	<2	3	6	<.2	.6	.6	17	.04	.044	31	11	.11	53	.003	<1	.84	.005	.06	1	<1	.9	<1	.02	4
00486	.5	18	18	51	.1	16	6	277	4.02	31	1	<2	6	4	.2	.9	.6	22	.05	.048	26	17	.20	59	.004	<1	1.05	.005	.07	1	<1	1.1	<1	.02	4
00487	.4	22	21	77	.1	23	9	275	3.33	26	2	<2	4	12	<.2	.8	<.5	21	.12	.055	27	19	.27	62	.004	<1	1.25	.005	.08	1	<1	1.3	<1	.02	3
00488	.5	40	21	73	.3	29	13	1099	2.88	24	11	<2	2	40	.3	<.5	<.5	17	.54	.094	20	18	.25	73	.009	<1	1.05	.006	.09	1	<1	2.2	<1	.04	3
00489	.6	44	19	72	.3	42	14	774	3.12	23	7	<2	2	28	.7	<.5	<.5	20	.45	.085	26	22	.29	66	.010	<1	1.16	.005	.07	<1	<1	2.6	1	.03	3
00490	3.5	40	66	125	.4	37	15	284	3.82	16	5	<2	6	34	1.2	.8	.9	28	.50	.089	40	26	.23	93	.004	<1	1.99	.009	.08	1	<1	2.4	<1	.03	4
00492	.5	22	27	53	.3	14	20	716	1.91	8	2	<2	1	26	.3	<.5	<.5	22	.32	.078	27	14	.17	119	.004	<1	1.13	.008	.06	1	<1	1.0	1	.04	5
00493	.4	19	12	56	.1	19	6	110	3.04	30	<1	<2	5	3	.2	.8	<.5	22	.02	.037	28	16	.25	55	.003	<1	1.10	.005	.09	1	<1	1.0	<1	.01	5
00494	1.2	27	13	90	.1	30	8	175	8.32	16	<1	<2	10	3	<.2	1.6	<.5	21	.02	.098	31	26	.21	37	.002	<1	1.68	.005	.05	<1	<1	1.4	2	.03	7
00496	.5	7	3	15	.1	6	2	53	.89	13	<1	<2	4	2	<.2	<.5	<.5	24	.03	.019	42	5	.02	10	.009	<1	.29	.004	.01	<1	<1	.5	1	<.01	6
00498	.6	5	6	11	<.1	3	1	35	.89	8	<1	<2	4	2	<.2	.8	<.5	10	.01	.016	30	4	.02	20	.005	3	.35	.003	.02	<1	<1	.4	1	<.01	5
00499	1.1	27	24	71	<.1	23	8	279	6.03	42	<1	<2	9	4	<.2	1.4	1.1	33	.04	.052	26	27	.17	50	.017	<1	1.00	.005	.07	1	<1	1.6	<1	.01	5
STANDARD C3	26.9	69	36	171	5.6	39	13	771	3.40	59	26	<2	21	29	24.2	15.0	23.3	81	.59	.099	18	184	.62	163	.086	24	1.88	.046	.19	15	2	4.5	1	.03	8
STANDARD G-2	1.5	2	2	44	<.1	7	4	501	1.92	1	2	<2	2	71	<.2	<.5	<.5	41	.62	.096	7	75	.58	217	.125	7	.89	.086	.54	2	1	2.5	<1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00500	.3	9	10	52	<.1	22	6	136	4.14	16	1	<2	13	2	<.2	1.4	.7	33	.02	.026	41	19	.41	25	.007	2	1.38	.006	.03	<1	<1	.7	<1	<.01	7
00530	.8	10	12	21	.7	7	2	146	1.58	15	<1	<2	1	6	<.2	<.5	<.5	18	.06	.059	23	10	.10	138	.006	4	.56	.006	.05	1	<1	.5	<1	.01	4
00531	2.9	47	21	85	1.4	36	14	569	3.12	24	3	<2	3	17	.4	1.1	<.5	29	.09	.075	21	26	.27	919	.007	4	1.39	.008	.11	1	1	2.2	1	.02	4
00532	1.4	16	13	54	.3	18	6	215	2.52	23	1	<2	3	9	.2	<.5	<.5	24	.09	.044	21	17	.23	382	.010	4	.83	.005	.07	1	<1	1.2	<1	<.01	3
00533	.4	33	18	70	<.1	32	13	455	3.36	23	1	<2	6	6	<.2	1.7	<.5	27	.05	.046	34	25	.47	163	.010	4	1.28	.006	.10	1	<1	2.8	<1	<.01	4
00534	.5	12	11	37	.2	12	5	197	1.85	12	<1	<2	1	6	<.2	.6	<.5	22	.05	.050	23	15	.19	141	.008	<1	.92	.006	.09	1	<1	1.0	<1	.01	4
00535	.4	42	24	80	.1	38	18	720	3.65	36	1	<2	10	44	.3	<.5	<.5	23	.78	.061	33	20	.41	93	.007	2	1.07	.008	.14	2	<1	3.4	<1	<.01	3
00536	1.1	46	20	95	.2	43	17	569	3.37	28	3	<2	10	25	.3	.8	<.5	27	.31	.070	29	20	.41	262	.024	<1	1.08	.009	.09	1	<1	3.4	1	<.01	3
00537	3.2	94	19	215	.3	90	19	540	4.20	19	24	<2	9	26	.6	1.5	<.5	35	.20	.076	26	23	.34	373	.050	<1	1.34	.007	.08	<1	<1	4.3	<1	.01	4
00540	1.2	70	22	135	.3	80	26	756	4.85	33	2	<2	9	29	.5	1.7	.6	25	.24	.101	26	31	.34	81	.009	<1	.94	.006	.07	1	<1	4.7	<1	.01	3
00541	.8	51	20	108	.2	51	17	583	3.76	30	2	<2	10	23	.4	1.7	.7	17	.21	.101	30	16	.26	42	.011	2	.61	.005	.06	1	<1	2.7	<1	.01	2
00542	.9	41	21	95	.2	51	17	850	3.66	32	2	<2	10	17	.4	1.6	.6	18	.18	.084	32	15	.28	57	.012	6	.70	.006	.06	1	<1	2.5	1	.01	2
00543	.4	42	24	85	.1	42	19	732	3.82	32	1	<2	13	24	.2	1.1	<.5	25	.30	.076	33	23	.51	83	.013	<1	1.22	.009	.12	1	<1	3.6	<1	<.01	4
00544	.6	40	22	84	1.8	41	14	507	3.53	25	2	<2	6	22	.3	1.0	<.5	25	.17	.107	26	24	.40	111	.005	<1	1.52	.008	.11	1	<1	3.5	1	.03	3
00545	.7	15	16	45	.4	16	5	162	2.82	18	1	<2	6	6	<.2	.7	<.5	24	.04	.057	27	19	.29	58	.006	2	1.07	.006	.07	1	<1	1.6	<1	<.01	4
RE 00545	.6	14	16	43	.4	16	6	161	2.82	17	1	<2	7	7	<.2	.7	<.5	23	.04	.056	25	19	.29	58	.006	3	1.06	.006	.07	1	<1	1.6	<1	<.01	4
00546	.7	20	20	57	<.1	23	9	252	3.64	25	1	<2	5	8	.2	.7	<.5	28	.06	.118	27	23	.38	65	.008	3	1.24	.006	.06	1	<1	1.8	<1	<.01	4
00547	.5	10	9	30	.5	9	2	80	1.76	16	<1	<2	<1	6	<.2	<.5	<.5	17	.02	.088	23	9	.07	30	.005	<1	.51	.004	.03	<1	<1	.5	<1	.01	4
00548	.2	2	4	7	.1	1	<1	13	.21	2	<1	<2	3	14	<.2	.5	<.5	6	.02	.016	30	3	.01	19	.003	<1	.26	.003	.02	<1	<1	.2	<1	<.01	4
00549	1.2	24	20	69	.3	19	6	188	3.37	29	1	<2	5	26	.2	1.4	.6	26	.04	.104	25	15	.15	72	.007	<1	.69	.005	.05	1	<1	1.4	<1	.01	2
00550	.7	24	33	56	.6	16	5	168	3.41	34	1	<2	3	11	.3	1.0	.7	24	.07	.061	18	18	.14	86	.005	<1	.87	.007	.07	1	<1	1.2	<1	.02	3
00551	.5	17	30	48	.2	15	5	140	2.88	26	1	<2	2	11	.2	.8	.8	24	.05	.064	21	15	.19	50	.005	3	.76	.005	.06	1	<1	1.0	<1	.02	3
00552	.3	30	67	92	.2	30	14	681	3.34	30	2	<2	3	17	.3	<.5	.9	25	.24	.076	22	21	.40	77	.005	1	1.24	.006	.09	1	<1	2.4	1	.02	4
00553	.3	34	66	89	.5	34	14	570	3.12	27	2	<2	4	18	.3	.6	<.5	22	.27	.075	23	19	.37	76	.005	2	1.18	.005	.08	1	<1	2.8	1	.02	3
00554	.2	41	89	97	.7	42	16	615	3.52	27	3	<2	5	15	.4	1.1	.6	23	.22	.100	26	23	.39	91	.004	<1	1.46	.006	.10	1	<1	3.3	1	.03	4
00555	.4	15	16	43	<.1	14	5	179	2.50	24	1	<2	1	8	.2	.6	<.5	21	.08	.066	22	14	.18	53	.008	1	.72	.006	.05	1	<1	.9	<1	.01	3
00556	.7	26	32	48	<.1	14	4	136	2.20	27	1	<2	1	10	.2	.7	.7	25	.05	.044	26	11	.07	42	.007	<1	.64	.006	.05	1	<1	.8	<1	.01	3
00557	.6	45	45	95	.8	43	19	592	3.88	50	3	<2	3	24	.5	.7	1.9	20	.30	.102	22	19	.26	67	.007	2	1.10	.006	.09	1	<1	2.5	<1	.02	3
00558	.6	33	42	83	.8	29	13	530	3.63	32	3	<2	2	22	.3	.9	1.0	22	.27	.089	24	20	.25	66	.006	<1	1.16	.006	.09	1	<1	2.1	<1	.02	3
00565	.6	23	30	62	.1	22	9	333	3.11	30	2	<2	1	18	.2	<.5	.5	24	.27	.063	23	17	.24	68	.006	<1	.91	.005	.07	1	<1	1.3	<1	.01	4
00567	.4	35	51	90	.4	34	17	624	3.91	26	3	<2	7	23	.3	.6	<.5	26	.29	.066	24	23	.37	90	.005	2	1.51	.006	.10	1	<1	3.1	1	.02	4
00568	.7	41	50	79	1.0	31	11	398	3.67	27	3	<2	3	19	.3	.7	.6	29	.34	.079	26	18	.18	86	.009	3	1.23	.007	.13	2	<1	1.8	<1	.02	3
00569	.7	26	63	72	.5	24	10	294	4.43	28	2	<2	1	13	.2	1.1	.7	32	.12	.087	21	25	.29	89	.007	<1	1.47	.007	.11	1	<1	1.6	<1	.02	5
00570	.4	20	29	60	.1	26	12	299	3.58	31	2	<2	5	12	.2	<.5	<.5	20	.17	.050	23	21	.34	62	.004	3	1.18	.006	.08	1	<1	1.8	<1	.01	3
STANDARD C3	26.8	69	36	173	5.5	38	12	780	3.31	59	26	2	21	29	24.4	16.1	23.4	82	.58	.100	18	181	.62	164	.090	25	1.86	.046	.19	15	2	4.5	1	.03	7
STANDARD G-2	1.5	2	2	44	<.1	7	4	506	1.95	<1	3	<2	5	69	<.2	<.5	<.5	40	.62	.101	8	77	.59	228	.127	<1	.88	.081	.55	2	1	2.4	1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

- considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00571	.3	5	10	15	<.1	5	1	41	1.08	13	<1	<2	2	5	<.2	<.5	<.5	16	.06	.020	30	6	.09	67	.006	2	.53	.005	.05	1	<1	.4	<1	<.01	5
00573	.3	10	11	34	.2	10	5	270	2.02	17	<1	<2	2	13	.2	<.5	<.5	19	.24	.034	26	12	.18	60	.008	1	.70	.006	.07	1	<1	.8	<1	<.01	5
00752	1.2	17	8	41	.1	14	4	154	2.46	73	1	<2	4	5	.5	<.5	<.5	24	.05	.041	25	7	.03	22	.004	2	.44	.007	.03	<1	<1	.8	<1	<.01	3
00753	.5	9	11	22	<.1	7	2	59	1.12	10	<1	<2	3	3	<.2	.5	<.5	22	.03	.020	35	7	.07	36	.010	2	.63	.005	.05	<1	<1	.5	1	<.01	6
00754	.3	21	21	64	.4	24	9	200	3.50	15	1	<2	7	16	<.2	1.5	<.5	29	.20	.047	23	27	.26	107	.007	2	1.99	.008	.10	<1	<1	2.0	<1	.02	5
00755	.5	20	18	55	.3	18	7	194	3.19	14	2	<2	4	6	.2	1.2	.5	22	.06	.058	31	17	.22	77	.007	<1	1.86	.008	.06	1	<1	1.3	<1	.03	5
00756	.5	19	5	39	.1	15	4	93	2.60	36	1	<2	6	6	<.2	1.2	.5	16	.01	.051	28	6	.02	17	.003	2	.50	.004	.03	1	<1	.8	<1	<.01	3
00758	.4	10	4	23	.1	9	2	59	1.93	21	<1	<2	2	3	<.2	.5	.5	24	.02	.047	35	8	.03	21	.005	1	.67	.005	.03	<1	<1	.5	<1	<.01	5
00759	.6	8	9	25	<.1	10	2	66	1.93	25	<1	<2	2	3	<.2	.8	.7	42	.03	.033	29	11	.04	23	.015	<1	.60	.004	.03	1	<1	.6	<1	.01	5
00760	.4	11	17	35	<.1	11	4	97	2.26	20	<1	<2	5	5	<.2	.6	.5	42	.06	.022	31	11	.06	48	.029	<1	.59	.006	.05	1	<1	.9	<1	<.01	5
00761	.4	49	46	84	.4	32	11	566	3.27	18	5	<2	2	21	.3	.6	.5	25	.26	.136	32	30	.32	132	.009	<1	1.91	.009	.12	2	1	1.5	1	.05	5
00762	1.8	90	36	89	1.0	50	37	1425	4.21	18	9	<2	6	31	1.0	.8	.5	25	.41	.173	66	31	.25	112	.010	2	2.49	.009	.09	1	<1	2.6	1	.07	4
00763	1.3	39	15	86	.4	29	16	1548	5.07	13	3	<2	5	55	1.0	.6	<.5	25	.86	.111	41	28	.20	82	.008	1	1.91	.007	.06	1	<1	2.0	2	.05	5
00764	1.4	23	20	84	.1	22	11	219	4.76	12	1	<2	4	25	<.2	.5	<.5	58	.34	.056	27	38	.46	84	.005	<1	1.70	.005	.04	<1	<1	2.8	<1	.02	9
00765	.8	52	28	89	.4	35	15	2116	3.78	17	6	<2	3	19	.3	.8	.8	29	.22	.074	33	27	.27	109	.012	4	1.48	.007	.07	<1	<1	2.6	1	.03	4
RE 00765	.8	53	30	91	.5	36	15	2309	3.99	17	6	<2	3	21	.3	.9	.7	29	.23	.077	34	28	.28	116	.012	<1	1.56	.008	.07	1	<1	2.7	<1	.04	4
00766	.4	9	12	23	<.1	8	3	80	2.50	22	<1	<2	2	3	<.2	<.5	.6	21	.02	.027	23	11	.07	28	.007	<1	.64	.005	.04	1	<1	.7	<1	<.01	3
00767	.3	16	19	48	.1	17	5	135	3.95	29	1	<2	4	4	<.2	.9	.5	20	.02	.055	23	18	.18	49	.005	2	.86	.005	.07	1	<1	1.0	<1	.02	2
00768	.4	17	24	60	.1	15	6	174	3.81	16	1	<2	6	6	<.2	1.5	<.5	22	.06	.055	29	16	.15	48	.004	<1	1.15	.006	.06	1	<1	1.1	1	.02	5
00769	.4	10	9	22	<.1	5	2	37	1.42	8	<1	<2	2	4	<.2	.5	<.5	16	.03	.023	27	8	.06	43	.006	<1	.65	.004	.03	<1	<1	.5	<1	<.01	4
00770	.6	104	36	86	.7	60	23	2096	4.77	30	12	<2	10	54	.4	1.1	1.1	24	.56	.132	93	31	.32	141	.006	1	2.11	.012	.21	1	<1	5.2	<1	.04	5
00771	.3	18	11	59	<.1	16	5	108	2.92	21	<1	<2	8	12	<.2	.6	<.5	22	.11	.031	37	11	.13	74	.004	3	.83	.005	.06	<1	<1	.9	<1	<.01	6
00772	.2	40	24	63	.5	53	18	326	3.58	24	5	<2	8	29	.2	.9	<.5	17	.31	.067	73	21	.36	47	.007	1	1.55	.006	.06	1	<1	2.3	<1	.02	4
00773	.5	55	27	71	.3	38	19	617	4.78	31	3	<2	3	34	.3	1.0	.6	34	.34	.077	59	27	.35	83	.009	<1	1.73	.007	.09	1	<1	2.6	1	.02	5
00774	.3	39	22	64	.3	21	18	672	3.35	19	3	<2	2	30	.2	<.5	<.5	31	.25	.079	26	21	.20	108	.011	2	1.13	.007	.08	1	<1	2.0	1	.02	5
00775	.3	38	27	95	.2	35	18	632	3.92	30	4	<2	5	22	.2	.8	.8	23	.27	.074	25	25	.39	108	.006	<1	1.43	.007	.13	1	<1	3.0	<1	.02	4
00776	.3	23	18	55	.3	16	8	335	2.71	22	1	<2	2	15	<.2	<.5	<.5	21	.18	.053	24	15	.19	81	.007	<1	.89	.007	.09	1	<1	1.1	<1	.01	4
00777	.7	71	36	108	1.3	61	21	1154	4.95	37	5	<2	6	34	.3	1.7	.6	28	.50	.146	36	28	.33	148	.006	2	2.26	.010	.20	1	<1	5.8	1	.05	5
STANDARD C3	25.4	64	34	160	5.2	36	11	737	3.20	55	25	<2	19	29	23.5	15.3	22.5	80	.57	.093	18	174	.59	154	.087	22	1.79	.044	.19	16	2	4.3	<1	.03	8
STANDARD G-2	1.5	2	2	45	<.1	7	4	517	1.99	1	2	<2	3	73	<.2	<.5	<.5	40	.64	.101	8	77	.60	226	.129	2	.90	.084	.56	2	1	2.6	<1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004326R Page 1

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: K. Ross

SAMPLE#	Au* ppb
00098	33.3
00099	151.4
00100	47.7
00208	40.8
00209	15.5
00210	50.5
00211	17.1
00212	13.1
00213	38.2
00214	55.2
00215	21.3
RE 00215	6.5
00216	13.5
00217	5.8
00218	10.4
00219	69.7
00220	176.5
00221	12.5
00222	3.4
00223	1.1
00224	4.2
00225	4.3
00226	11.9
00227	14.7
00228	1.2
00229	6.8
00230	210.2
00231	13.4
00232	15.6
00233	9.0
00234	248.5
00235	12.2
00236	17.5
00237	141.0
STANDARD DS2	201.3

AU* BY ACID LEACHED, ANALYSIS BY ICP/MS. (10 gm)
- SAMPLE TYPE: SOIL PULP
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: NOV 23 2000 DATE REPORT MAILED: Nov 27/00 SIGNED BY. D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data FA

SAMPLE#	Au* ppb
00238	6.4
00239	1.5
00240	33.6
00241	176.6
00242	57.9
00243	13.7
00244	60.6
00245	7.8
00246	18.1
00247	192.7
00248	30.7
00249	80.8
00250	3.3
RE 00250	7.7
00251	7.8
00252	30.0
00253	20.0
00254	21.1
00255	30.3
00256	17.6
00257	23.0
00302	7.1
00303	4929.4
00304	2888.3
00305	36.1
00306	78.1
00307	92.1
00308	31.6
00309	37.9
00310	121.6
00311	55.2
00312	14.5
00313	9.8
00314	20.8
STANDARD DS2	195.4

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA

SAMPLE#	Au* ppb
00315	16.6
00316	75.5
00317	34.3
00318	65.0
00319	136.3
00320	162.3
00322	34.9
00323	58.5
00324	22.7
00325	189.7
00326	25.8
00327	7.3
00328	35.2
00331	28.7
00332	113.0
00333	216.7
00334	32.1
00335	29.8
RE 00335	53.1
00337	15.5
00338	36.1
00339	95.3
00340	16.3
00341	40.1
00342	33.5
00343	37.7
00344	30.7
00345	33.1
00346	55.0
00347	73.7
00348	273.3
00349	28.5
00350	90.5
00352	54.5
STANDARD DS2	209.7

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ___

SAMPLE#	Au* ppb
00353	25.2
00354	72.4
00355	12.7
00356	42.3
00358	20.2
00359	17.4
00360	5.9
00361	17.9
00362	8.1
00363	5.3
00364	6.7
00365	4.1
RE 00365	4.5
00366	6.4
00367	9.5
00368	12.9
00369	22.2
00370	37.7
00371	122.3
00372	32.6
00373	24.8
00374	38.3
00375	18.4
00376	34.8
00377	18.8
00378	15.7
00379	19.8
00380	4.2
00381	3.7
00382	10.4
00383	19.1
00384	13.9
00385	10.0
00386	12.7
STANDARD DS2	190.2

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Au* ppb
00387	58.5
00388	59.6
00389	33.5
00390	72.8
00391	33.0
00392	18.0
00393	23.6
00394	193.9
00395	24.9
00396	20.1
00397	70.5
00398	121.0
00400	3.3
RE 00400	6.8
00401	36.2
00402	6.4
00403	36.6
00404	9.1
00406	55.9
00407	37.2
00408	9.1
00409	10.7
00412	43.8
00413	6.9
00414	26.1
00415	9.8
00416	57.2
00417	34.7
00418	24.2
00419	19.6
00420	17.4
00421	21.0
00422	107.6
00423	19.6
STANDARD DS2	201.6

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ____

SAMPLE#	Au* ppb
00424	155.0
00425	126.2
00426	297.4
00428	8.1
00429	46.4
00433	2.1
00434	5.8
00435	9.8
00436	8.8
00438	34.4
00439	48.7
00440	162.3
00441	19.6
00442	55.9
00443	44.7
00444	122.2
00445	26.5
RE 00445	57.9
00446	51.2
00447	48.8
00448	52.9
00449	67.9
00450	155.7
00451	44.7
00452	39.6
00453	23.4
00454	140.5
00455	56.1
00456	139.3
00457	150.7
00458	55.7
00460	32.7
00461	9.3
00462	7.3
STANDARD DS2	215.9

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data__/ FA ____

SAMPLE#	Au* ppb
00463	14.3
00464	6.0
00465	11.1
00466	50.7
00467	7.7
00469	26.4
00470	14.5
00471	34.3
00472	33.6
00473	34.8
00474	31.0
00475	6.9
RE 00477	13.8
00476	75.5
00477	4.5
00478	3.5
00479	35.7
00480	5.2
00481	4.3
00482	27.3
00483	9.3
00484	11.9
00485	23.6
00486	12.0
00487	8.0
00488	56.0
00489	43.3
00490	104.0
00492	4.8
00493	20.0
00494	6.0
00496	35.1
00498	15.1
00499	157.8
STANDARD DS2	198.1

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au* ppb
00500	.9
00530	25.1
00531	33.4
00532	73.1
00533	45.8
00534	26.8
00535	26.4
00536	54.7
00537	6.2
00540	71.2
00541	56.9
00542	320.7
00543	84.9
00544	32.9
00545	233.0
RE 00545	13.1
00546	27.2
00547	657.7
00548	20.1
00549	19.6
00550	78.2
00551	57.4
00552	25.2
00553	86.1
00554	24.3
00555	77.8
00556	23.9
00557	161.5
00558	72.8
00565	21.7
00567	16.6
00568	6.5
00569	18.2
00570	42.9
STANDARD DS2	198.4

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA

SAMPLE#	Au* ppb
00571	11.1
00573	20.1
00752	87.5
00753	11.2
00754	49.0
00755	31.1
00756	52.2
00758	8.2
00759	26.0
00760	29.4
00761	9.6
00762	7.2
00763	7.2
00764	23.7
00765	17.8
RE 00765	11.5
00766	15.0
00767	15.1
00768	8.2
00769	8.7
00770	60.9
00771	7.8
00772	14.7
00773	62.6
00774	16.2
00775	8.0
00776	13.8
00777	14.2
STANDARD DS2	204.0

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. COUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) 3-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004381 Page 1

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: K. Ross

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00258	.2	31	138	93	.3	30	11	402	3.42	27	2	<2	6	13	<.2	<.5	.5	21	.16	.058	29	20	.36	87	.003	<1	1.42	.005	.08	1	<1	2.6	<1	.02	3
00260	.3	18	17	53	.6	16	6	325	2.41	18	1	<2	2	24	<.2	<.5	<.5	19	.43	.065	24	13	.17	98	.006	3	.82	.006	.10	1	<1	1.3	<1	.03	3
00261	.4	35	32	70	1.1	35	13	814	3.45	26	3	<2	5	31	.2	<.5	.5	24	.56	.096	24	21	.36	98	.006	<1	1.38	.006	.10	1	<1	3.3	<1	.04	3
00262	.2	36	33	77	1.0	37	15	876	3.80	28	3	<2	5	27	.2	.6	.5	22	.44	.101	25	23	.40	100	.006	<1	1.49	.006	.11	2	<1	3.7	1	.03	3
00263	.5	12	13	42	.2	10	4	169	2.68	25	1	<2	2	15	<.2	<.5	.5	24	.26	.039	24	12	.15	70	.006	<1	.71	.003	.06	1	<1	.9	<1	.01	3
00264	.3	22	20	57	.2	20	7	158	4.23	34	1	<2	5	4	<.2	<.5	.6	15	.03	.044	24	18	.25	47	.004	<1	.99	.002	.05	2	<1	1.1	1	.01	2
00265	.4	11	16	35	.1	12	4	120	3.62	30	1	<2	4	3	<.2	.7	.6	22	.04	.065	22	15	.18	41	.004	<1	.81	.003	.05	2	<1	.8	<1	.02	2
00266	.2	6	13	20	.2	8	2	59	2.18	22	<1	<2	3	3	<.2	<.5	<.5	24	.02	.045	22	10	.12	31	.005	<1	.66	.002	.04	3	<1	.6	<1	.02	3
00267	<.2	21	43	75	.2	24	13	1892	3.45	26	2	<2	2	22	.2	<.5	<.5	30	.41	.070	24	22	.31	95	.009	<1	1.28	.005	.07	1	<1	2.2	2	.02	4
00268	.2	33	458	111	.7	28	13	1688	3.18	24	4	<2	2	32	.5	.5	1.3	27	.72	.091	19	18	.22	64	.010	<1	1.32	.005	.06	1	<1	2.8	1	.04	3
00269	.6	24	19	58	.1	19	7	142	3.99	51	2	<2	7	19	<.2	.8	.6	31	.37	.035	29	13	.12	52	.008	<1	.84	.003	.04	2	<1	1.6	1	.01	3
00270	.2	49	19	63	.5	22	11	853	3.39	17	4	<2	2	34	<.2	<.5	<.5	27	.69	.089	38	18	.22	61	.011	<1	1.30	.006	.05	1	<1	2.9	<1	.04	3
00271	.8	50	11	63	.3	12	9	249	5.68	18	2	<2	3	16	<.2	<.5	<.5	62	.28	.058	21	14	.22	61	.009	<1	1.16	.003	.03	1	<1	2.1	<1	.03	5
00272	.2	18	28	75	.5	26	9	221	3.10	10	3	<2	2	25	<.2	<.5	<.5	30	.38	.069	18	20	.27	69	.014	<1	1.41	.005	.04	1	<1	1.7	<1	.03	3
RE 00272	.3	18	28	75	.5	26	9	223	3.17	10	3	<2	2	25	<.2	<.5	<.5	30	.38	.068	18	20	.28	68	.015	<1	1.43	.005	.04	1	<1	1.8	<1	.03	3
00274	.7	25	22	65	.1	23	9	472	3.58	13	2	<2	4	20	<.2	<.5	<.5	27	.25	.072	26	20	.25	69	.005	<1	1.54	.004	.05	1	<1	1.4	<1	.02	4
00275	.2	23	17	73	.3	26	8	275	3.27	26	1	<2	6	11	<.2	<.5	<.5	23	.12	.042	28	23	.33	117	.004	<1	1.54	.005	.10	1	<1	1.7	1	.01	4
00276	<.2	26	36	86	.5	22	9	95	2.40	9	3	<2	5	33	<.2	<.5	<.5	20	.40	.084	32	17	.17	128	.004	<1	2.14	.005	.06	1	<1	1.8	<1	.04	4
00277	.6	29	23	58	.2	13	5	143	4.92	7	2	<2	8	11	<.2	<.5	.5	31	.16	.071	44	18	.14	76	.005	1	1.30	.003	.05	1	<1	.8	1	.03	7
00278	.4	16	19	51	.1	15	5	138	3.12	10	1	<2	6	6	<.2	<.5	<.5	24	.04	.037	38	14	.19	62	.005	<1	1.12	.002	.04	1	<1	.7	1	.02	4
00279	.3	16	15	62	.2	13	6	422	2.99	7	3	<2	7	32	<.2	<.5	<.5	14	.35	.062	47	12	.20	128	.003	<1	1.08	.004	.05	1	<1	1.2	<1	.03	3
00280	.9	23	25	92	.4	21	9	226	5.98	12	3	<2	9	27	<.2	<.5	<.5	26	.31	.075	47	21	.31	110	.004	<1	1.76	.004	.04	1	<1	1.3	<1	.03	5
00281	.3	11	16	36	<.1	10	3	98	2.84	10	<1	<2	8	9	<.2	<.5	<.5	22	.06	.049	57	11	.15	52	.003	<1	1.18	.003	.04	1	<1	.7	<1	.02	4
00282	.3	6	8	22	.1	6	1	61	1.79	18	<1	<2	6	6	<.2	<.5	<.5	28	.05	.045	38	8	.08	35	.003	1	.93	.002	.03	1	<1	.7	<1	.01	5
00283	.5	7	10	34	<.1	7	4	192	2.09	10	<1	<2	4	5	<.2	<.5	<.5	28	.03	.037	40	10	.25	47	.005	<1	1.01	.002	.05	1	<1	.8	1	<.01	5
00284	.3	15	22	39	<.1	12	4	227	3.44	8	1	<2	2	8	<.2	<.5	<.5	25	.07	.044	24	15	.14	73	.007	<1	.96	.003	.03	1	<1	.8	<1	.02	3
00285	1.5	22	13	68	.2	22	12	603	3.66	15	3	<2	4	24	.2	<.5	<.5	22	.41	.111	44	19	.30	67	.005	<1	1.50	.005	.04	1	<1	1.7	<1	.04	4
00286	.8	19	22	80	.1	18	7	156	2.91	19	1	<2	2	9	<.2	<.5	<.5	28	.07	.055	38	21	.32	73	.006	<1	1.60	.005	.05	1	<1	1.1	<1	.02	4
00287	.4	7	5	34	.2	7	2	85	2.46	8	<1	<2	4	4	<.2	<.5	<.5	31	.04	.070	26	12	.13	33	.004	1	1.24	.002	.03	1	<1	.7	<1	.02	6
00288	.3	8	7	41	.2	10	2	93	4.13	13	1	<2	4	4	<.2	.5	<.5	55	.04	.084	24	25	.20	43	.008	<1	1.53	.003	.03	2	<1	.9	1	.02	6
00289	<.2	4	4	20	.2	4	<1	36	4.03	14	1	<2	6	2	<.2	<.5	<.5	39	.02	.053	12	14	.11	28	.003	<1	1.38	.003	.02	2	<1	.7	1	.02	5
00290	.3	6	2	13	.2	4	1	39	.89	5	<1	<2	6	2	<.2	<.5	<.5	16	.02	.031	27	4	.02	12	.002	2	.87	.002	.02	1	<1	.5	<1	<.01	5
00291	.3	7	2	14	.3	5	2	35	.95	6	<1	<2	5	2	<.2	<.5	<.5	16	.02	.030	25	4	.03	11	.002	<1	.87	.002	.02	1	<1	.5	<1	<.01	5
00292	.2	3	<2	7	.1	2	1	22	.38	3	<1	<2	6	2	<.2	<.5	<.5	10	.02	.019	30	3	.02	11	.002	<1	.89	.003	.02	<1	<1	.4	<1	<.01	5
STANDARD C3	26.6	65	34	164	5.2	34	11	757	3.16	60	26	<2	21	28	22.2	18.1	22.6	77	.57	.092	21	170	.59	156	.083	19	1.87	.040	.16	15	<1	4.5	<1	.03	6
STANDARD G-2	1.5	3	3	45	<.1	7	3	543	2.05	<1	4	<2	5	81	<.2	<.5	<.5	41	.68	.104	10	81	.61	248	.129	<1	1.06	.113	.52	3	<1	2.8	<1	<.01	4

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
- SAMPLE TYPE: SOIL SS80 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 30 2000 DATE REPORT MAILED: Nov 9/00 SIGNED BY. J. Wang

D. TOYE, C. LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00293	.6	10	15	25	<.1	8	2	87	1.74	8	<1	<2	3	3	<.2	<.5	<.5	24	.02	.049	31	11	.11	38	.005	<1	.98	.004	.03	1	<1	.7	<1	.01	4
00294	.6	9	14	25	.1	7	2	85	1.72	9	<1	<2	3	3	<.2	<.5	<.5	30	.02	.040	33	10	.10	40	.006	<1	1.06	.004	.03	1	<1	.7	1	.01	5
00295	.4	10	15	26	.1	7	2	100	1.96	8	<1	<2	3	4	<.2	<.5	<.5	29	.03	.043	33	11	.11	44	.006	<1	1.06	.004	.03	1	<1	.7	1	.01	4
00296	.4	8	15	18	.2	5	1	56	1.60	8	<1	<2	5	3	<.2	<.5	<.5	24	.02	.029	32	9	.06	32	.006	<1	1.00	.004	.02	1	<1	.7	<1	.01	4
00298	.5	6	3	12	.1	4	1	27	.62	8	<1	<2	4	4	<.2	<.5	<.5	16	.04	.015	33	5	.02	23	.003	1	.29	.003	.02	1	<1	.6	<1	<.01	3
00299	.3	20	19	62	.1	16	6	161	4.79	23	1	<2	7	5	<.2	.5	<.5	27	.04	.039	32	19	.20	57	.009	<1	.95	.003	.05	2	<1	1.1	<1	.02	3
00300	.3	20	17	62	<.1	13	4	153	3.20	10	1	<2	7	7	<.2	<.5	<.5	21	.04	.052	36	14	.15	83	.004	1	1.16	.004	.05	1	<1	1.1	<1	.02	3
00501	.6	22	18	69	.3	20	8	343	4.13	32	1	<2	3	12	<.2	.5	<.5	31	.09	.102	24	21	.22	59	.010	<1	.86	.004	.06	2	<1	1.4	1	.01	2
00502	.2	13	16	34	.6	10	3	153	2.56	20	1	<2	2	6	<.2	<.5	<.5	25	.05	.116	26	15	.18	54	.007	<1	.76	.005	.06	1	<1	.8	1	.01	3
00503	.3	7	9	12	.4	4	1	118	1.37	11	<1	<2	<1	5	<.2	<.5	<.5	17	.03	.062	27	9	.05	38	.007	<1	.40	.003	.03	1	<1	.3	<1	.01	2
00504	.4	20	15	51	.3	15	6	410	2.52	27	1	<2	1	11	<.2	.7	.6	25	.05	.078	24	16	.12	82	.006	<1	.75	.004	.07	2	<1	.8	1	.01	2
00505	.6	16	14	46	.1	13	6	841	2.07	27	<1	<2	2	11	.2	.7	.6	24	.05	.045	27	14	.10	85	.007	3	.57	.003	.05	1	<1	.8	2	.01	2
00506	.5	32	32	70	.7	29	12	713	3.10	41	2	<2	3	36	.2	.7	.7	25	.29	.094	23	21	.22	97	.005	3	1.01	.006	.10	2	<1	2.7	<1	.02	2
00507	.7	28	31	75	.3	25	8	254	3.62	57	1	<2	3	26	.2	.9	.5	33	.07	.088	22	19	.17	85	.008	<1	.80	.005	.08	2	<1	1.7	1	.02	2
00508	1.2	49	43	86	1.5	37	24	2671	4.25	88	4	<2	2	53	.6	1.3	.8	34	.38	.197	18	25	.24	134	.007	<1	1.52	.007	.12	2	<1	3.2	1	.05	3
00509	.8	22	20	66	1.7	18	6	317	4.39	42	1	<2	4	18	<.2	.8	<.5	34	.08	.249	25	21	.19	60	.010	<1	.81	.004	.05	2	<1	1.5	1	.02	2
00510	2.3	37	23	98	1.2	29	9	304	3.93	28	2	<2	2	45	.2	1.4	<.5	27	.09	.106	19	21	.22	68	.007	<1	.96	.004	.06	2	<1	1.4	<1	.05	1
RE 00510	2.3	39	24	102	1.2	31	9	314	4.01	30	2	<2	2	47	.2	1.3	<.5	28	.09	.110	21	21	.22	72	.007	<1	.99	.005	.07	2	<1	1.5	1	.05	2
00511	.6	7	11	24	.5	6	3	405	1.54	12	<1	<2	<1	8	<.2	<.5	<.5	20	.04	.083	29	11	.12	76	.006	<1	.61	.003	.04	1	<1	.5	<1	.01	3
00512	.2	15	15	47	.6	14	5	185	3.89	20	1	<2	5	5	<.2	<.5	<.5	29	.04	.096	26	24	.29	60	.008	2	1.19	.004	.05	2	<1	1.4	1	.02	3
00513	.4	7	8	18	.4	6	2	79	1.61	13	<1	<2	3	4	<.2	<.5	<.5	20	.02	.044	32	12	.12	32	.006	<1	.61	.003	.04	3	<1	.6	<1	<.01	3
00514	.3	11	9	24	.3	11	3	248	1.69	11	1	<2	1	17	<.2	<.5	<.5	16	.23	.057	28	12	.20	47	.006	<1	.60	.004	.04	2	<1	.9	<1	.01	3
00515	.2	51	25	86	.2	49	21	938	4.06	47	2	<2	12	34	<.2	.5	<.5	28	.55	.069	34	29	.45	91	.006	<1	1.12	.007	.13	3	<1	4.2	<1	.01	2
00516	.5	44	21	87	.2	42	17	775	3.77	32	2	<2	10	40	.2	<.5	<.5	25	.59	.079	31	20	.39	69	.012	3	.85	.006	.08	2	<1	3.6	<1	.02	2
00517	6.7	83	20	146	.2	74	26	1483	7.40	19	5	<2	11	22	.7	1.3	<.5	14	.20	.120	23	12	.14	97	.003	<1	.46	.003	.06	2	<1	2.5	1	.05	<1
00518	.6	46	37	105	.2	51	24	1224	4.16	34	2	<2	12	29	.2	.5	<.5	21	.39	.077	33	17	.31	86	.011	<1	.74	.005	.07	2	<1	3.3	1	<.01	2
00519	.9	55	22	92	.2	46	19	789	4.04	39	3	<2	11	38	.2	1.2	<.5	18	.42	.082	33	15	.24	61	.013	2	.64	.006	.06	2	<1	3.2	<1	.02	1
00523	.9	41	21	78	.2	36	15	627	3.17	31	2	<2	10	22	.2	.7	<.5	25	.24	.070	33	16	.32	125	.020	<1	.75	.006	.07	2	<1	2.8	<1	<.01	2
00524	1.1	45	18	89	.2	42	16	668	3.29	30	3	<2	9	25	.2	1.0	<.5	26	.23	.073	33	18	.34	276	.024	3	.78	.007	.07	1	<1	2.9	1	<.01	2
00525	1.5	47	20	108	.3	47	17	602	3.52	23	4	<2	11	22	.2	.6	<.5	25	.21	.072	34	17	.32	282	.024	<1	.80	.006	.06	1	<1	3.1	1	<.01	2
00526	1.7	47	21	126	.4	57	18	650	3.66	22	6	<2	11	25	.2	1.0	<.5	26	.21	.066	30	18	.34	413	.025	<1	.91	.007	.07	1	<1	3.4	<1	<.01	2
00527	2.1	46	16	93	.3	41	15	513	3.35	19	3	<2	7	35	<.2	1.2	<.5	44	.35	.065	23	30	.50	427	.061	1	1.39	.013	.08	1	<1	4.6	2	.01	3
00528	.3	43	22	83	.2	36	17	687	3.76	38	1	<2	12	22	<.2	.7	<.5	28	.20	.068	37	18	.39	92	.010	<1	1.03	.007	.12	2	<1	3.6	<1	<.01	2
00559	<.2	41	161	102	1.0	50	17	650	3.99	31	4	<2	6	18	.3	<.5	.7	22	.27	.072	30	24	.37	81	.004	<1	1.54	.005	.09	2	<1	3.3	1	.02	3
STANDARD C3	26.7	68	35	171	5.3	37	11	799	3.39	61	27	3	22	30	23.1	16.0	23.4	82	.60	.096	22	179	.62	162	.089	23	1.81	.043	.17	14	1	4.7	<1	.03	6
STANDARD G-2	1.5	3	2	46	<.1	7	4	558	2.08	<1	4	<2	4	75	<.2	<.5	<.5	44	.68	.104	11	81	.63	236	.134	3	.91	.082	.50	2	<1	2.8	<1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data /, FA ____

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00560	.3	47	104	98	1.0	49	18	769	4.37	29	5	<2	9	20	.2	<.5	.6	31	.28	.067	36	27	.51	76	.006	2	1.72	.009	.12	2	<1	4.7	<1	.02	6
00561	.3	23	66	73	.5	17	6	189	3.53	23	1	<2	5	7	<.2	<.5	.6	35	.05	.048	32	19	.21	76	.007	<1	1.35	.005	.08	2	<1	2.0	<1	.01	6
00562	<.2	33	123	112	.5	35	17	624	4.00	28	3	<2	9	9	<.2	<.5	.5	25	.11	.075	31	23	.44	68	.004	<1	1.54	.005	.09	2	<1	3.3	<1	.02	5
00564	.3	35	71	93	.5	36	18	627	3.91	32	3	<2	8	17	<.2	<.5	<.5	29	.24	.071	34	24	.47	91	.009	2	1.56	.008	.12	1	<1	3.6	<1	.01	5
00575	1.8	58	33	92	.2	57	25	691	4.70	107	3	<2	8	16	.3	1.0	3.7	19	.28	.079	20	20	.39	55	.019	1	.65	.004	.06	4	<1	2.7	<1	.44	3
00576	.8	45	21	79	.2	42	15	496	3.73	30	2	<2	8	12	<.2	.9	1.0	28	.18	.078	35	31	.40	71	.028	<1	.98	.004	.05	2	<1	3.6	<1	.02	4
00577	.8	34	16	84	.2	40	18	715	3.85	20	2	<2	4	16	<.2	1.0	<.5	27	.24	.063	29	31	.38	75	.014	<1	1.08	.003	.04	1	<1	2.6	<1	.02	4
00578	.6	34	21	97	.8	36	16	1503	3.41	10	5	<2	2	34	.7	<.5	<.5	25	.55	.165	20	38	.37	139	.010	<1	1.08	.005	.05	1	<1	3.7	<1	.07	4
00579	.6	77	20	160	1.0	57	20	1313	4.09	16	9	<2	2	49	.5	1.0	.5	32	.70	.193	20	40	.40	150	.015	2	1.43	.005	.05	1	<1	5.1	<1	.06	4
00580	.6	58	19	109	.8	47	23	1728	4.15	14	4	<2	2	38	.6	<.5	<.5	36	.48	.171	25	42	.47	106	.014	1	1.35	.003	.04	1	<1	5.8	1	.05	5
00581	.5	58	15	112	1.0	49	20	1915	4.17	13	3	<2	2	42	.6	.6	<.5	40	.56	.177	23	43	.46	105	.013	<1	1.40	.005	.04	1	<1	4.6	<1	.05	5
00582	1.0	33	13	64	.5	34	14	484	4.86	29	1	5	2	12	<.2	1.2	<.5	34	.15	.101	25	37	.30	58	.018	<1	.79	.001	.03	1	<1	1.9	1	.02	5
00583	1.5	51	18	115	.4	55	20	856	4.46	35	2	<2	2	17	.4	1.0	.7	29	.19	.108	24	30	.31	62	.010	<1	.99	.002	.05	1	<1	2.5	<1	.03	4
00585	.4	4	5	18	.4	5	2	486	.81	2	<1	<2	3	6	<.2	<.5	<.5	15	.08	.041	35	14	.09	78	.016	<1	.44	.001	.03	<1	<1	.8	<1	<.01	4
00586	.7	17	9	52	.2	32	9	419	4.04	13	1	<2	2	5	<.2	.8	<.5	49	.10	.168	23	54	.33	65	.016	<1	.89	<.001	.04	2	<1	2.0	<1	.02	5
00587	.8	14	8	74	.6	34	11	328	4.20	17	1	<2	2	13	<.2	.5	<.5	41	.17	.081	24	53	.39	104	.016	<1	1.05	.001	.03	1	<1	2.0	<1	.02	5
00588	.5	41	16	124	.4	58	18	1284	3.73	11	2	<2	2	24	.5	.9	<.5	38	.47	.149	22	51	.40	91	.011	1	1.03	.001	.03	1	<1	3.2	<1	.04	4
00589	.7	31	14	68	.1	35	12	568	3.55	11	1	<2	5	8	<.2	.9	<.5	22	.13	.149	27	29	.33	39	.017	<1	.77	<.001	.03	1	<1	1.6	<1	.01	3
00591	.5	21	17	52	.1	31	8	218	3.94	9	1	<2	4	4	<.2	<.5	<.5	35	.04	.089	24	40	.28	50	.013	<1	.86	<.001	.03	1	<1	1.7	<1	.02	4
00592	.5	14	11	55	.1	28	7	332	3.49	9	1	<2	4	5	<.2	<.5	<.5	37	.04	.085	21	64	.33	49	.013	<1	1.17	.001	.03	1	<1	2.1	<1	.02	4
RE 00592	.3	14	11	54	.1	28	7	327	3.44	8	1	<2	4	5	<.2	.6	<.5	37	.04	.086	22	64	.33	49	.013	<1	1.16	<.001	.03	1	<1	2.0	1	.02	4
00593	.6	39	21	81	.4	62	20	1132	4.11	9	3	<2	3	42	<.2	.7	<.5	36	.86	.128	16	72	.53	80	.008	1	1.14	.001	.04	1	<1	5.2	<1	.07	4
00594	.5	18	15	50	.2	32	12	665	2.97	6	3	<2	2	63	<.2	.6	<.5	23	1.04	.107	13	33	.37	62	.008	2	.81	<.001	.03	1	<1	2.2	<1	.07	2
00595	.3	15	20	45	.1	18	5	157	3.61	8	1	<2	3	5	<.2	.5	<.5	17	.05	.068	20	17	.22	32	.007	<1	.79	<.001	.03	1	<1	.7	<1	.03	2
00596	.5	10	12	46	.2	14	4	195	3.20	8	1	<2	3	7	<.2	<.5	<.5	24	.09	.075	25	22	.26	63	.013	<1	.98	<.001	.03	1	<1	.9	<1	.01	3
00597	.5	17	18	62	<.1	22	6	172	4.51	10	1	<2	7	7	<.2	.9	<.5	22	.09	.060	28	25	.27	70	.019	<1	.97	<.001	.03	2	<1	1.4	1	.01	3
00598	.4	12	14	36	.2	13	4	126	2.32	4	1	<2	4	5	<.2	<.5	<.5	15	.05	.042	22	11	.12	50	.008	<1	.63	<.001	.03	1	<1	.7	<1	.01	2
00599	.7	16	17	58	.2	19	5	309	3.84	12	1	<2	4	7	<.2	.7	<.5	27	.10	.092	25	23	.24	68	.024	<1	.92	<.001	.03	2	<1	1.1	1	.02	2
00600	1.7	37	21	81	.2	36	15	511	3.18	17	3	<2	5	14	<.2	1.2	<.5	15	.13	.066	25	13	.18	50	.007	<1	.54	.001	.05	1	<1	1.6	<1	.03	1
00602	.7	17	25	60	.2	9	5	138	3.11	10	2	<2	5	25	<.2	.5	<.5	28	.25	.055	46	13	.18	140	.005	<1	1.25	.002	.05	1	<1	1.6	<1	.03	4
00603	.6	22	29	63	.2	27	11	1344	3.80	13	5	<2	5	31	.5	<.5	<.5	17	.53	.111	43	15	.16	68	.005	<1	1.21	.002	.05	1	<1	2.9	<1	.05	2
00604	1.1	61	36	83	.5	48	17	1341	4.09	21	9	<2	7	27	.7	.6	<.5	22	.43	.168	66	23	.27	80	.010	<1	1.78	.004	.08	1	<1	3.5	<1	.06	3
00605	<.2	37	22	81	.3	26	8	329	2.85	8	3	<2	6	20	.4	<.5	.5	21	.26	.083	45	22	.38	119	.006	<1	1.59	.004	.08	1	<1	1.9	<1	.03	4
00606	<.2	15	17	50	.2	14	3	90	3.77	14	2	<2	7	9	<.2	<.5	<.5	26	.16	.051	26	20	.21	96	.004	<1	1.38	.002	.05	1	<1	1.3	<1	.03	4
STANDARD C3	28.2	70	36	176	5.7	37	11	819	3.46	60	27	3	24	29	25.0	18.0	23.8	87	.59	.095	22	177	.64	155	.091	23	1.89	.044	.19	15	1	5.0	1	.03	7
STANDARD G-2	1.7	2	5	46	<.1	8	4	557	2.04	<1	4	<2	4	96	<.2	<.5	<.5	43	.73	.104	11	83	.63	256	.129	<1	1.28	.105	.54	2	<1	2.8	<1	<.01	6

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA ____

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00607	.4	19	13	52	<.1	18	5	129	4.18	118	<1	<2	6	5	.2	.9	<.5	26	.05	.045	41	9	.04	36	.005	2	.63	.004	.06	2	<1	1.4	<1	.01	5
00608	4.6	18	25	26	<.1	20	3	68	3.33	21	<1	<2	6	5	<.2	1.0	.7	27	.05	.056	43	13	.03	43	.007	<1	.81	.004	.09	2	<1	1.0	1	<.01	5
00609	.7	14	8	34	.1	12	4	115	2.47	32	<1	<2	4	4	.2	<.5	<.5	47	.03	.046	33	9	.03	20	.016	<1	.59	.001	.03	1	<1	.8	<1	<.01	5
00610	.4	4	4	12	<.1	5	2	59	1.14	7	<1	<2	4	2	.3	<.5	.5	32	.03	.015	30	7	.02	18	.009	<1	.57	.001	.02	1	<1	.7	<1	<.01	6
00611	.5	6	4	18	<.1	7	2	54	1.41	19	<1	<2	4	6	.2	<.5	<.5	24	.02	.030	30	6	.02	15	.005	<1	.53	.001	.03	1	<1	.6	<1	<.01	4
00612	.4	14	21	50	.1	18	9	940	3.03	16	2	<2	2	27	.2	<.5	.5	27	.38	.068	24	18	.19	121	.007	<1	1.31	.004	.06	1	<1	1.4	<1	.03	4
00613	.2	9	13	46	.1	9	4	216	1.37	7	1	<2	4	18	.2	<.5	<.5	17	.19	.033	38	13	.19	142	.007	<1	1.31	.005	.07	<1	<1	1.4	<1	<.01	4
00614	.3	15	22	50	.1	19	9	778	2.73	15	2	<2	3	28	<.2	.6	<.5	23	.37	.077	26	19	.19	116	.006	<1	1.31	.003	.06	1	<1	1.4	<1	.03	4
00615	.2	17	22	52	.1	23	8	609	2.92	17	2	<2	4	28	<.2	.5	.6	22	.37	.083	31	20	.21	118	.005	<1	1.43	.004	.07	1	<1	1.7	<1	.03	4
00616	.2	16	21	49	.1	19	8	605	2.84	15	2	<2	3	26	<.2	<.5	<.5	23	.34	.072	27	18	.20	109	.005	<1	1.30	.003	.06	2	<1	1.5	<1	.03	4
00617	.4	15	22	53	.1	19	10	1308	3.14	16	2	<2	3	31	<.2	<.5	<.5	26	.44	.081	23	19	.19	130	.006	<1	1.39	.004	.06	1	<1	1.5	<1	.04	4
00618	.2	23	21	82	.3	28	9	286	3.68	21	1	<2	11	16	<.2	<.5	<.5	15	.19	.066	50	22	.32	107	.002	<1	1.46	.005	.10	1	<1	1.5	<1	.02	4
00620	.3	38	29	82	.3	28	14	1406	3.40	21	13	<2	3	63	.4	<.5	.7	23	.81	.127	29	22	.23	104	.011	<1	1.38	.005	.08	2	<1	2.5	<1	.06	4
00621	.2	30	23	107	.3	26	15	588	3.80	17	4	<2	11	28	<.2	<.5	<.5	20	.34	.098	54	22	.39	84	.004	<1	1.65	.003	.07	1	<1	2.5	<1	.03	5
00622	.4	17	32	86	.1	20	8	242	4.08	17	2	<2	8	33	<.2	<.5	.6	23	.48	.059	46	21	.36	86	.004	<1	1.39	.003	.06	1	<1	1.6	<1	.02	6
00623	.5	42	27	89	.3	37	14	1149	4.08	17	5	<2	3	44	.4	<.5	<.5	28	.60	.113	54	23	.24	89	.012	<1	1.46	.004	.06	1	<1	2.7	<1	.05	5
00624	.4	35	17	91	.5	25	11	466	3.93	14	4	<2	5	24	.2	<.5	<.5	43	.30	.128	43	20	.45	98	.007	<1	1.86	.004	.06	1	<1	2.7	<1	.05	5
00625	.3	14	6	53	.1	12	4	118	3.02	19	<1	<2	9	5	<.2	<.5	<.5	28	.03	.036	48	15	.18	53	.004	<1	.99	.001	.05	1	<1	.9	<1	.01	6
00626	<.2	12	14	34	.1	10	3	97	3.05	6	<1	<2	10	5	<.2	<.5	<.5	19	.03	.030	39	11	.12	46	.004	<1	1.07	<.001	.05	1	<1	.8	<1	<.01	4
RE 00626	.3	11	14	34	.1	9	3	95	3.01	6	<1	<2	10	5	<.2	<.5	<.5	18	.03	.030	38	11	.12	45	.004	<1	1.05	<.001	.05	1	<1	.7	<1	<.01	4
00627	.2	11	12	31	.1	8	3	83	2.85	6	<1	<2	9	4	<.2	<.5	<.5	21	.03	.032	36	10	.11	41	.004	<1	1.00	<.001	.04	1	<1	.7	<1	<.01	4
00628	<.2	14	13	42	.1	11	3	103	3.81	8	1	<2	10	4	<.2	<.5	.6	24	.03	.047	32	14	.16	39	.005	<1	1.10	<.001	.04	2	<1	.7	1	.01	5
00629	.2	54	40	70	.1	25	11	142	4.88	40	1	<2	8	4	<.2	.9	1.4	15	.02	.073	49	10	.06	29	.004	<1	.72	.001	.04	2	<1	.9	1	.02	3
00632	.3	16	19	36	.1	12	4	159	3.81	31	1	<2	7	3	<.2	.6	.6	29	.03	.040	33	14	.10	39	.007	<1	.77	<.001	.06	2	<1	1.0	1	<.01	4
00633	.6	59	44	56	1.6	43	9	825	3.23	18	11	<2	5	68	.4	<.5	.5	30	.85	.276	57	40	.26	123	.010	<1	2.31	.005	.06	1	<1	3.7	<1	.14	5
00634	<.2	11	7	14	<.1	5	2	89	.86	3	1	<2	5	7	<.2	<.5	<.5	8	.09	.020	24	6	.07	69	.003	<1	.59	.001	.03	<1	<1	1.2	<1	<.01	2
00635	.2	12	7	13	<.1	6	2	130	.88	3	1	<2	6	7	.2	<.5	<.5	8	.09	.020	23	6	.07	70	.004	<1	.57	.001	.03	1	<1	1.3	<1	<.01	2
00636	<.2	4	2	5	<.1	1	<1	15	.28	8	<1	<2	6	3	<.2	<.5	<.5	7	.03	.012	34	3	.02	19	.003	<1	.55	<.001	.02	<1	<1	.4	<1	<.01	3
00637	.4	17	21	40	.3	15	4	170	3.13	25	1	<2	2	5	<.2	.6	.5	32	.06	.048	25	14	.12	47	.016	<1	.84	.001	.05	2	<1	1.0	<1	.02	3
00638	.9	3	2	9	.2	3	1	21	.39	1	<1	<2	7	3	<.2	<.5	<.5	6	.02	.017	33	3	.01	31	.003	<1	.19	<.001	.02	<1	<1	.3	1	<.01	2
00639	.9	5	4	11	<.1	4	1	27	.67	6	<1	<2	3	3	.2	<.5	<.5	15	.01	.025	27	4	.03	39	.003	<1	.31	<.001	.02	1	<1	.5	<1	<.01	4
00640	1.3	7	6	15	.1	5	1	46	1.12	11	<1	<2	2	4	.2	.5	<.5	29	.01	.057	26	7	.04	51	.005	<1	.37	<.001	.03	1	<1	.6	<1	<.01	4
00641	.5	8	10	21	.4	7	2	67	1.77	11	1	<2	1	4	<.2	<.5	<.5	18	.02	.064	19	12	.12	56	.005	<1	.68	<.001	.04	1	<1	.5	<1	.02	2
00642	.6	11	12	28	.4	10	3	85	2.23	14	1	<2	1	4	<.2	<.5	<.5	21	.02	.061	20	15	.15	58	.005	<1	.80	<.001	.05	1	<1	.7	<1	.02	2
STANDARD C3	27.0	67	35	169	5.6	36	11	796	3.36	58	26	2	22	29	24.0	17.8	23.1	84	.59	.096	21	178	.62	162	.086	22	1.80	.042	.17	15	1	4.7	<1	.03	7
STANDARD G-2	1.6	2	4	44	<.1	8	4	543	2.01	<1	3	<2	5	86	<.2	<.5	<.5	41	.68	.102	10	80	.61	254	.126	5	1.04	.142	.55	3	<1	2.7	<1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00643	.9	11	13	32	.2	12	3	143	2.14	15	1	<2	1	6	.3	<.5	<.5	29	.04	.051	24	14	.15	79	.008	<1	.60	.003	.06	1	<1	.6	<1	.02	4
00644	.4	15	15	44	.7	16	7	345	2.12	10	1	<2	1	24	.3	<.5	<.5	24	.19	.077	23	17	.35	272	.005	1	1.13	.005	.10	1	<1	1.1	<1	.02	5
00645	.5	17	16	53	.5	19	11	458	2.62	12	1	<2	2	21	.3	<.5	<.5	28	.17	.068	25	19	.41	237	.006	<1	1.23	.004	.10	1	<1	1.4	<1	.02	5
00646	.4	15	13	49	.3	17	7	291	2.57	11	1	<2	2	15	.3	<.5	<.5	27	.13	.059	25	18	.40	179	.007	<1	1.18	.003	.09	2	<1	1.4	<1	.01	5
00647	.5	16	20	61	.1	36	12	720	2.12	6	2	<2	16	11	.4	<.5	<.5	4	.11	.064	31	7	.21	112	.002	<1	.54	<.001	.04	1	<1	1.1	1	<.01	2
00648	.4	16	21	60	.1	37	13	752	2.13	5	2	<2	15	10	.4	<.5	<.5	4	.11	.060	30	7	.21	122	.002	<1	.55	<.001	.05	1	<1	1.1	<1	<.01	2
00649	1.3	34	27	91	.2	62	19	1334	3.26	13	3	<2	14	9	.5	<.5	<.5	10	.07	.045	38	9	.18	167	.007	1	.60	.001	.06	1	<1	1.9	1	<.01	2
00650	.7	35	29	90	.2	53	18	1085	3.34	16	3	<2	12	11	.4	.6	<.5	15	.10	.051	43	13	.27	134	.012	1	.69	.001	.06	2	<1	2.1	1	<.01	3
00651	2.6	73	23	160	.5	110	37	2598	5.51	29	2	<2	8	54	1.1	1.9	<.5	28	.63	.152	30	18	.38	144	.008	5	.94	.005	.06	2	<1	6.0	1	.01	4
00652	1.8	65	17	131	.3	104	38	2200	5.80	19	2	<2	7	44	.6	1.3	<.5	30	.68	.144	30	35	.50	119	.007	2	1.03	.003	.05	1	<1	6.5	1	.01	5
00654	5.4	129	18	177	1.1	214	68	3111	8.87	40	4	<2	5	61	1.3	9.2	.6	44	.55	.249	17	25	.25	170	.006	3	.86	.004	.07	2	<1	14.0	1	.01	6
00655	.3	45	32	87	.1	42	20	666	4.03	27	2	<2	12	63	.2	.6	<.5	34	1.27	.070	34	26	.63	88	.026	2	1.40	.012	.14	1	<1	4.3	<1	<.01	5
00656	.6	21	21	43	.4	14	4	202	2.88	26	1	<2	1	18	.3	<.5	<.5	31	.27	.051	26	17	.15	114	.007	<1	.82	.002	.07	1	<1	1.0	<1	.02	4
00657	.5	21	21	41	.3	13	4	269	2.64	23	1	<2	1	15	.4	.5	<.5	30	.22	.050	31	16	.15	102	.008	<1	.83	.002	.07	1	<1	1.0	<1	.01	4
RE 00657	.6	21	21	41	.3	13	4	274	2.61	24	1	<2	1	14	.3	<.5	<.5	29	.21	.050	30	16	.15	101	.007	<1	.82	.002	.07	1	<1	1.0	<1	.01	4
00701	1.5	36	19	88	.2	40	16	737	3.39	16	3	<2	6	23	.4	1.4	<.5	12	.24	.064	28	11	.20	68	.005	1	.48	.001	.04	1	<1	1.8	<1	.02	2
00702	1.4	24	21	53	.6	20	6	219	3.69	14	1	<2	2	6	.3	.8	<.5	40	.09	.084	20	18	.12	67	.032	<1	.56	.001	.02	1	<1	1.2	<1	.03	3
00703	1.5	24	15	55	.5	19	6	300	2.65	14	1	<2	2	5	.3	.9	<.5	42	.06	.067	22	13	.09	57	.030	<1	.42	<.001	.02	1	<1	1.1	<1	.01	3
00704	.4	17	16	65	.2	23	8	392	3.01	8	2	<2	3	18	.2	<.5	<.5	21	.20	.073	25	19	.32	58	.009	<1	.99	<.001	.03	1	<1	1.7	<1	.02	3
00705	1.5	19	18	56	.2	20	5	229	3.33	11	2	<2	2	59	.2	1.0	<.5	34	.40	.142	22	18	.21	56	.018	<1	.62	.001	.03	1	<1	1.1	<1	.03	4
00707	1.3	21	11	74	.4	21	11	1025	4.46	33	1	<2	4	6	.3	1.2	.8	25	.06	.195	26	24	.21	60	.009	<1	.94	<.001	.03	2	<1	1.3	<1	.02	3
00708	1.3	16	14	56	.5	20	5	157	4.05	18	1	<2	4	5	.2	.8	<.5	30	.05	.150	24	32	.25	49	.005	<1	.91	<.001	.03	2	<1	1.2	<1	.02	3
00709	.8	10	9	38	.4	11	3	125	2.87	13	<1	<2	5	4	.3	<.5	<.5	24	.03	.157	25	26	.18	39	.006	<1	.89	<.001	.02	1	<1	1.0	<1	.02	4
00710	1.1	17	15	64	.3	21	5	166	5.00	17	1	<2	3	4	.2	<.5	<.5	30	.05	.144	21	31	.23	46	.010	<1	.91	<.001	.02	2	<1	1.3	<1	.03	4
00711	1.3	24	14	69	1.1	23	6	136	4.80	18	1	<2	4	5	<.2	.5	<.5	41	.04	.143	21	35	.26	51	.005	<1	1.21	<.001	.02	1	<1	1.7	<1	.02	4
00712	1.3	29	15	87	1.0	33	9	239	5.21	23	1	<2	5	6	.2	1.0	<.5	27	.08	.114	22	35	.30	44	.011	1	1.11	<.001	.02	1	<1	1.8	<1	.02	4
00713	1.7	19	18	58	1.0	17	4	203	4.30	16	1	<2	1	8	.5	1.2	<.5	30	.07	.295	16	24	.15	65	.006	<1	.60	<.001	.02	1	<1	.5	<1	.03	3
00714	1.3	29	11	75	.5	33	11	360	4.38	22	1	<2	2	17	.3	.9	.5	31	.18	.062	22	33	.29	68	.008	<1	1.00	<.001	.02	1	<1	1.6	<1	.02	3
00715	1.4	46	17	113	.8	56	16	612	4.23	28	2	<2	2	26	.5	1.0	<.5	28	.27	.119	21	32	.32	94	.007	1	.95	.001	.04	1	<1	2.0	<1	.03	3
00716	1.4	67	18	131	.4	75	26	728	4.99	27	2	<2	5	25	.5	1.2	<.5	29	.26	.081	29	39	.42	91	.007	<1	1.13	.001	.04	1	<1	3.9	<1	.02	3
00717	.7	44	11	131	.3	43	15	2379	3.81	15	2	<2	1	36	.7	.8	.5	28	.42	.138	19	33	.29	151	.006	<1	.96	.003	.05	1	<1	2.1	<1	.04	3
00718	1.1	23	9	79	.8	27	10	1051	3.81	12	1	<2	2	5	.5	.6	<.5	33	.06	.127	21	35	.26	72	.010	<1	.86	<.001	.03	1	<1	1.3	<1	.02	3
00719	1.0	18	10	43	.6	19	5	144	2.94	11	1	<2	1	7	.4	.6	<.5	37	.08	.089	18	31	.16	73	.008	<1	.66	<.001	.02	1	<1	.8	<1	.03	4
00720	.9	27	20	80	.3	32	10	388	5.03	16	2	<2	2	19	.3	.5	.6	41	.34	.092	22	37	.30	120	.016	<1	.98	.001	.05	1	<1	1.7	<1	.02	4
STANDARD C3	28.1	68	36	178	5.6	38	12	808	3.41	60	27	2	23	30	25.1	18.4	23.9	84	.61	.100	22	180	.64	167	.086	21	1.84	.041	.17	15	1	4.7	<1	.03	7
STANDARD G-2	1.6	2	3	46	<.1	8	4	555	2.05	<1	3	<2	5	83	.2	<.5	<.5	43	.70	.106	11	80	.63	251	.129	2	1.01	.121	.53	2	<1	2.8	<1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00721	.8	38	22	87	.1	37	17	900	4.48	18	2	<2	3	13	.2	.7	.5	37	.21	.077	27	37	.33	92	.018	4	1.05	.006	.07	2	<1	2.3	<1	.01	3
00722	.6	41	22	92	.3	46	16	659	3.66	17	2	<2	3	31	.2	.6	.6	30	.73	.088	24	33	.38	93	.016	6	1.07	.007	.06	1	<1	3.6	<1	.03	3
00723	.7	28	14	90	.1	43	16	583	5.00	13	2	<2	2	24	.2	<.5	<.5	38	.55	.072	21	67	.47	118	.011	<1	1.30	.005	.05	1	<1	2.7	<1	.03	4
00724	.6	19	20	53	.1	24	7	181	3.36	13	1	<2	3	9	<.2	1.1	<.5	20	.09	.056	24	23	.23	53	.009	<1	.76	.003	.04	2	<1	1.1	<1	.02	2
00725	.8	25	12	59	.2	35	8	621	2.89	16	2	<2	2	24	<.2	.6	.8	24	.35	.057	25	16	.16	76	.013	1	.62	.005	.06	1	<1	1.5	<1	.02	2
00726	.4	6	8	21	.1	5	3	238	.73	5	<1	<2	3	7	<.2	<.5	<.5	10	.06	.038	32	7	.05	57	.006	2	.45	.003	.05	<1	<1	.5	<1	<.01	2
00727	.6	20	13	69	.2	24	8	292	3.32	15	1	<2	4	7	<.2	<.5	<.5	24	.04	.057	29	23	.23	87	.010	<1	.96	.004	.06	1	<1	1.5	<1	.01	3
00728	.3	16	17	41	.2	17	5	183	2.78	10	1	<2	5	5	<.2	<.5	<.5	28	.03	.038	26	24	.18	94	.005	<1	.87	.003	.05	1	<1	1.3	<1	.01	3
00729	.4	14	16	47	.1	18	7	181	3.73	11	1	<2	6	9	<.2	.5	<.5	23	.11	.030	25	23	.22	86	.010	3	.93	.004	.03	1	<1	1.4	<1	.01	2
00730	.5	4	6	13	.1	5	1	51	.84	3	<1	<2	7	6	<.2	<.5	<.5	20	.04	.016	30	10	.06	41	.006	<1	.75	.004	.02	<1	<1	.9	<1	<.01	4
00732	.9	10	17	30	.7	7	2	261	3.24	8	1	<2	2	6	<.2	<.5	<.5	33	.04	.059	23	18	.13	64	.024	5	.67	.002	.02	1	<1	.8	<1	.02	3
00733	.9	27	16	54	.4	24	9	362	2.59	11	3	<2	4	21	<.2	1.0	<.5	17	.22	.054	23	13	.23	49	.019	2	.63	.002	.02	1	<1	1.6	<1	.02	2
00734	.5	22	29	77	.1	23	13	901	3.68	11	2	<2	3	38	<.2	.6	<.5	28	.29	.054	24	19	.34	65	.011	3	.88	.005	.05	1	<1	1.8	<1	.02	3
00735	1.2	17	16	48	.1	17	6	365	3.36	11	1	<2	2	7	<.2	.9	<.5	24	.07	.103	22	19	.22	53	.014	1	.78	.002	.02	1	<1	.9	<1	.02	2
00736	.5	25	15	76	.3	29	11	599	3.42	10	1	<2	4	8	.2	.6	<.5	28	.08	.066	29	25	.44	111	.012	4	1.13	.005	.05	1	<1	1.9	<1	.01	3
RE 00736	.4	26	16	80	.3	30	11	622	3.57	11	1	<2	4	8	.2	<.5	<.5	28	.09	.069	30	26	.45	118	.013	3	1.19	.005	.05	1	<1	2.0	1	.01	3
00780	.3	27	25	71	.4	31	14	431	3.66	31	3	<2	6	26	.2	<.5	<.5	20	.27	.063	33	20	.31	74	.005	4	1.24	.005	.09	2	<1	2.4	<1	.02	2
00781	.2	28	23	72	<.1	30	15	470	3.58	33	2	<2	8	14	<.2	<.5	<.5	20	.14	.046	36	20	.38	57	.007	1	1.13	.005	.08	1	<1	2.0	<1	<.01	3
00782	.3	53	31	78	.7	39	15	716	4.00	30	8	<2	6	31	.3	<.5	.8	28	.28	.095	98	25	.28	104	.007	3	1.81	.006	.11	1	<1	3.6	<1	.03	4
00783	.3	43	30	79	.5	28	16	1138	3.75	22	5	<2	2	28	<.2	<.5	<.5	28	.27	.083	56	24	.30	117	.009	1	1.40	.005	.09	1	<1	2.5	<1	.03	4
00784	.4	16	19	51	.1	16	7	181	3.24	28	1	<2	3	10	<.2	1.0	<.5	24	.10	.043	27	16	.24	52	.007	1	.92	.003	.06	1	<1	1.3	<1	.01	3
00785	<.2	48	30	76	.6	35	16	710	3.89	30	5	<2	4	36	.2	.6	<.5	28	.44	.101	39	24	.38	93	.007	<1	1.47	.005	.10	1	<1	3.6	<1	.03	3
00786	.2	34	23	61	.4	23	11	636	3.31	26	3	<2	3	33	.2	<.5	<.5	24	.40	.067	28	19	.27	109	.007	1	1.13	.005	.10	1	<1	2.2	<1	.01	3
00787	.3	.21	21	54	.3	19	9	444	2.80	21	2	<2	4	21	<.2	<.5	<.5	23	.23	.053	27	17	.30	81	.007	6	.97	.005	.08	1	<1	1.9	<1	.01	3
00788	.4	37	32	78	.5	28	13	934	3.87	28	4	<2	2	38	.2	<.5	.5	28	.37	.123	25	20	.25	136	.006	4	1.30	.005	.11	2	<1	2.7	<1	.04	4
00789	.3	27	22	73	.2	27	12	418	3.42	35	2	<2	6	13	<.2	<.5	<.5	16	.17	.044	32	17	.33	59	.008	1	.96	.005	.08	1	<1	2.1	<1	<.01	2
00790	.2	35	32	85	.2	29	16	807	4.07	30	3	<2	6	15	<.2	<.5	<.5	24	.13	.080	33	22	.31	109	.006	<1	1.42	.005	.09	2	<1	3.0	<1	.02	3
00791	<.2	25	14	59	.2	31	15	401	3.81	27	2	<2	7	11	<.2	<.5	<.5	24	.17	.037	31	21	.50	58	.006	4	1.32	.005	.07	2	<1	2.5	<1	<.01	3
00792	.3	41	30	79	.4	29	15	1094	3.82	28	3	<2	5	18	<.2	<.5	<.5	28	.28	.096	30	22	.30	81	.009	1	1.28	.005	.09	1	<1	3.1	<1	.02	3
00793	.4	25	26	67	.4	20	9	435	3.84	26	1	<2	1	11	<.2	<.5	<.5	32	.15	.064	29	19	.24	70	.010	4	1.06	.005	.08	1	<1	1.2	<1	.01	3
00794	.4	28	26	69	.4	27	11	342	4.58	29	1	<2	7	7	<.2	.7	<.5	31	.05	.054	31	25	.44	90	.007	4	1.51	.005	.10	2	<1	2.2	<1	.01	4
00796	.9	33	31	52	.5	22	10	388	3.92	23	2	<2	2	20	<.2	1.0	<.5	36	.38	.057	34	16	.17	60	.009	1	.98	.005	.06	2	<1	1.5	<1	.02	4
00797	.9	26	26	56	.2	20	8	304	3.79	27	1	<2	2	18	<.2	1.1	.5	35	.30	.051	29	16	.16	63	.015	1	.75	.005	.06	2	<1	1.5	<1	.01	4
00798	1.3	38	41	94	1.5	33	16	720	6.15	43	2	<2	4	16	<.2	1.1	.6	35	.23	.145	24	26	.28	89	.013	<1	1.32	.005	.09	2	<1	2.6	<1	.02	4
STANDARD C3	28.3	67	38	176	5.5	37	11	812	3.45	60	28	2	22	31	23.7	18.0	23.8	81	.61	.098	22	174	.63	169	.086	22	1.85	.041	.18	15	1	4.8	<1	.03	7
STANDARD G-2	1.5	3	5	46	<.1	8	3	563	2.10	<1	4	<2	5	102	<.2	<.5	<.5	43	.76	.105	11	81	.63	278	.134	3	1.22	.130	.62	2	<1	3.0	<1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00799	.2	26	18	65	.2	26	11	218	3.41	24	1	<2	7	8	<.2	.5	<.5	27	.08	.044	28	22	.32	50	.009	3	1.35	.006	.06	2	<1	2.0	<1	<.01	5
00800	<.2	16	23	55	.2	20	7	266	3.25	24	1	<2	3	7	<.2	<.5	<.5	24	.10	.090	23	20	.39	83	.006	1	1.11	.003	.06	2	<1	1.3	<1	.01	4
00820	.5	49	24	92	.2	52	21	1169	4.14	49	2	<2	10	27	<.2	1.1	<.5	28	.34	.078	36	23	.44	87	.016	3	1.20	.009	.11	2	<1	3.9	<1	<.01	4
00821	4.1	90	22	237	.9	171	42	3593	6.23	53	5	<2	7	33	1.1	3.6	.5	27	.47	.144	21	34	.33	257	.006	1	.93	.003	.05	2	<1	6.7	<1	<.01	4
00822	4.6	100	28	265	.9	191	49	3724	5.67	64	5	<2	8	34	1.3	4.2	<.5	28	.34	.153	24	24	.19	310	.008	3	.69	.003	.07	2	<1	6.0	1	<.01	3
00823	2.0	19	18	47	.5	15	4	202	3.88	12	1	<2	2	7	<.2	.7	<.5	26	.02	.081	21	18	.16	71	.009	2	.78	<.001	.04	2	<1	.7	<1	.02	4
00824	1.3	14	18	43	.3	14	4	147	4.42	15	1	<2	3	4	<.2	.8	<.5	24	.03	.063	20	20	.17	56	.009	<1	.84	.001	.04	2	<1	.8	<1	.02	4
00825	.9	14	16	37	.2	12	4	208	3.60	13	1	<2	3	3	<.2	<.5	<.5	22	.02	.041	22	16	.13	66	.010	1	.78	<.001	.04	2	<1	.8	<1	.01	3
00826	.8	27	18	68	.3	28	11	787	2.67	14	2	<2	3	17	<.2	.8	<.5	17	.15	.040	20	13	.21	206	.008	1	.79	.001	.06	1	<1	1.4	<1	.01	3
00827	1.8	21	15	56	.1	22	8	325	2.61	15	1	<2	3	13	<.2	.9	<.5	20	.09	.032	22	16	.24	237	.009	1	.79	.002	.06	1	<1	1.3	<1	<.01	3
00828	1.4	15	14	37	.2	12	5	359	2.18	10	1	<2	1	15	<.2	.6	<.5	25	.10	.037	23	14	.13	200	.012	<1	.64	.001	.05	1	<1	.7	<1	<.01	3
00829	.8	20	17	52	.5	21	10	527	2.98	14	1	<2	2	17	<.2	<.5	<.5	26	.16	.057	28	21	.38	246	.008	1	1.16	.003	.08	2	<1	1.7	<1	.01	4
00830	.5	35	26	77	.9	35	16	647	3.70	18	3	<2	5	20	<.2	<.5	<.5	31	.22	.070	31	27	.51	274	.009	1	1.43	.003	.09	1	<1	3.3	<1	.01	4
00831	.6	27	26	66	1.4	26	12	340	3.65	19	4	<2	4	39	<.2	.5	<.5	25	.45	.069	29	24	.45	348	.006	3	1.24	.003	.08	2	<1	2.8	<1	.04	4
00832	.4	24	28	73	.4	30	15	591	3.50	18	2	<2	5	19	<.2	<.5	<.5	31	.19	.067	30	23	.45	289	.009	2	1.36	.002	.09	2	<1	3.3	<1	.02	4
RE 00832	.3	24	29	73	.5	29	15	586	3.49	18	2	<2	5	19	<.2	<.5	<.5	32	.19	.067	30	24	.45	290	.009	2	1.37	.003	.09	1	<1	3.3	<1	.02	4
00833	.3	31	21	82	.1	50	19	813	3.52	12	3	<2	14	11	<.2	1.5	<.5	4	.10	.043	30	7	.08	126	.004	3	.52	.001	.07	1	<1	1.7	<1	<.01	1
00834	.3	32	23	79	.2	44	17	846	3.36	14	3	<2	14	13	<.2	.9	<.5	11	.15	.056	29	10	.16	142	.011	2	.63	.002	.07	1	<1	2.2	<1	<.01	2
00835	.5	37	25	88	.2	44	17	784	3.72	17	3	<2	15	15	<.2	1.0	<.5	16	.18	.062	35	13	.25	164	.016	<1	.86	.005	.08	1	<1	2.8	<1	<.01	2
00836	.5	34	25	80	.1	39	15	627	3.47	17	2	<2	13	13	<.2	.6	.5	16	.14	.053	34	14	.27	127	.016	1	.83	.004	.07	1	<1	2.6	<1	<.01	2
01201	.4	14	19	37	.2	12	5	261	2.65	23	1	<2	5	5	<.2	<.5	<.5	29	.05	.089	21	13	.11	50	.013	1	.63	<.001	.04	2	<1	1.1	<1	.01	3
01202	.5	27	34	67	.2	25	7	199	4.36	35	1	<2	7	8	<.2	.6	.5	22	.05	.073	24	22	.23	65	.008	1	.93	.001	.05	3	<1	1.7	<1	.01	3
01203	.7	27	17	61	.2	44	9	254	3.35	58	1	<2	2	9	.2	1.7	<.5	25	.11	.045	20	19	.13	69	.008	<1	.67	.001	.04	2	<1	1.3	<1	.01	3
01204	.4	45	31	78	2.1	52	16	1865	4.25	42	3	<2	4	33	.3	.5	.8	33	.44	.116	31	29	.31	129	.006	1	1.91	.006	.13	2	<1	4.8	<1	.03	5
01205	.2	15	22	47	.1	16	6	147	3.38	24	1	<2	3	7	<.2	.5	<.5	30	.08	.059	24	22	.29	77	.008	<1	1.05	.001	.05	2	<1	1.4	<1	.02	4
01206	.3	7	9	20	.1	7	2	75	1.33	10	<1	<2	3	4	<.2	<.5	<.5	21	.06	.026	23	9	.12	58	.005	2	.69	.001	.03	1	<1	.9	<1	.01	3
01207	<.2	35	26	77	1.0	42	14	608	3.65	26	3	<2	4	17	.2	<.5	<.5	27	.18	.093	26	23	.36	96	.005	<1	1.49	.003	.08	2	<1	3.4	<1	.03	3
01208	.3	31	28	72	.3	31	14	599	3.17	31	2	<2	5	17	<.2	.6	<.5	21	.17	.060	27	18	.32	69	.007	<1	1.07	.002	.07	2	<1	2.7	<1	.01	3
01209	.8	28	35	63	.6	21	7	281	4.21	42	1	<2	3	14	<.2	1.3	.6	45	.12	.104	20	17	.10	53	.027	<1	.64	.001	.05	2	<1	1.4	1	.02	3
01210	.5	29	20	61	.2	22	8	208	2.59	29	1	<2	2	18	<.2	1.1	<.5	24	.12	.052	21	13	.13	64	.010	1	.66	.002	.06	1	<1	1.3	<1	.01	2
01211	.2	44	24	85	.1	42	19	681	3.86	31	2	<2	12	56	<.2	<.5	<.5	28	1.02	.069	31	25	.57	90	.021	3	1.35	.012	.14	2	<1	3.9	<1	<.01	3
01212	<.2	43	33	82	.2	39	18	800	3.86	23	2	<2	11	21	<.2	<.5	<.5	31	.27	.070	37	23	.51	80	.015	4	1.40	.007	.14	2	<1	4.1	<1	<.01	3
01213	3.9	54	20	219	.6	142	44	2294	6.99	67	4	<2	10	31	1.1	6.7	1.0	29	.22	.131	30	25	.15	112	.009	4	.53	.003	.07	1	<1	7.6	<1	<.01	4
01214	1.1	43	33	162	.4	89	17	2965	4.03	35	4	<2	9	17	1.8	.7	.6	24	.18	.081	27	21	.35	151	.030	2	1.06	.007	.10	2	<1	3.5	<1	<.01	2
STANDARD C3	27.6	65	35	169	5.3	36	11	783	3.30	58	27	3	21	29	22.6	18.3	23.1	81	.58	.094	21	175	.61	159	.082	22	1.85	.042	.17	16	1	4.5	<1	.03	7
STANDARD G-2	1.4	3	3	45	<.1	7	4	542	2.00	<1	3	<2	4	75	<.2	<.5	<.5	40	.66	.102	10	79	.61	240	.125	2	.99	.103	.50	2	<1	2.5	<1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

ACME ANALYTICAL

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD FILE # A004381

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01215	.7	47	35	98	.2	49	21	960	4.01	28	2	<2	12	32	<.2	.7	<.5	30	.91	.071	36	23	.49	96	.023	4	1.21	.014	.15	1	<1	4.5	<1<.01	3
01216	1.7	48	33	124	.3	62	27	1491	4.15	44	3	<2	11	18	.7	1.2	<.5	21	.20	.087	33	19	.25	78	.027	1	.75	.008	.08	2	<1	3.3	1<.01	2
01218	.8	40	22	92	.2	45	17	619	3.56	19	4	<2	12	24	<.2	1.0	<.5	22	.29	.063	34	19	.39	160	.020	<1	.93	.009	.09	1	<1	3.3	<1<.01	2
01219	1.0	43	22	93	.3	46	19	793	3.72	21	4	<2	12	37	<.2	.8	<.5	26	.65	.064	32	21	.45	197	.026	2	1.06	.012	.11	1	<1	4.0	<1 .02	3
01220	.4	20	17	63	<.1	25	13	502	2.09	6	2	<2	17	29	.2	.9	<.5	5	.86	.062	36	7	.13	81	.002	2	.43	.004	.07	1	<1	2.5	<1 .04	1
01221	.9	48	22	97	.2	47	19	778	3.90	25	3	<2	11	23	<.2	1.0	<.5	35	.32	.072	34	26	.50	327	.036	7	1.25	.012	.11	2	<1	4.1	<1<.01	3
01222	.9	47	22	87	.2	43	19	678	3.77	27	3	<2	11	56	<.2	.7	<.5	33	1.08	.072	32	25	.52	292	.034	1	1.28	.014	.13	1	<1	4.3	<1<.01	3
01223	<.2	41	22	82	.1	38	18	642	3.88	29	2	<2	12	49	<.2	.7	<.5	29	.88	.074	35	24	.52	109	.026	6	1.22	.016	.14	1	<1	4.1	<1<.01	3
01224	1.0	21	16	55	.4	21	10	421	2.85	19	3	<2	4	9	<.2	<.5	<.5	27	.09	.046	27	20	.29	273	.008	<1	1.03	.004	.05	2	<1	1.9	<1 .01	2
01225	1.1	25	17	59	.6	26	11	526	3.26	20	5	<2	3	25	<.2	.5	<.5	29	.19	.055	31	23	.35	420	.010	3	1.19	.005	.07	1	<1	2.1	<1 .01	3
01226	1.2	20	16	65	.5	24	11	557	3.28	20	3	<2	3	21	<.2	.6	<.5	29	.13	.051	28	24	.35	407	.010	<1	1.15	.005	.07	1	<1	1.7	<1 .01	3
01227	1.2	25	20	62	.9	24	9	386	3.18	20	4	<2	2	13	<.2	<.5	<.5	30	.06	.074	27	24	.31	343	.008	<1	1.43	.006	.10	1	<1	2.1	2 .02	3
01228	.9	43	26	88	.2	44	18	846	3.76	21	2	<2	13	17	<.2	<.5	<.5	22	.20	.055	39	22	.42	170	.021	3	1.16	.010	.12	1	<1	3.4	<1<.01	3
01229	.7	37	24	82	.1	39	17	817	3.51	20	2	<2	11	14	<.2	<.5	<.5	23	.16	.055	39	23	.40	126	.018	<1	1.00	.007	.09	2	<1	3.1	1<.01	2
01232	1.0	44	23	99	.1	49	19	860	3.50	22	3	<2	11	20	.3	1.3	<.5	27	.20	.077	37	20	.35	156	.037	<1	.87	.007	.06	1	<1	3.4	1<.01	2
01234	1.2	53	31	114	.4	82	25	1167	4.61	39	3	<2	10	18	.3	1.3	<.5	26	.18	.088	31	33	.34	78	.011	6	.88	.008	.09	2	<1	4.4	1<.01	2
01236	.8	49	27	90	.3	63	22	1016	4.31	28	2	<2	7	23	.2	.7	<.5	36	.35	.086	31	40	.48	79	.009	<1	1.16	.007	.09	2	<1	4.8	<1 .01	3
01237	1.8	83	26	130	.2	156	48	2847	6.08	35	2	<2	8	54	.5	1.8	<.5	34	.74	.123	28	73	.53	155	.011	2	1.13	.008	.09	2	<1	7.1	2<.01	4
01238	2.9	79	12	153	.2	103	43	3147	4.69	56	3	<2	9	30	.9	1.6	<.5	9	.37	.122	29	9	.14	95	.003	5	.56	.006	.06	3	<1	4.2	2<.01	1
01239	.2	52	43	85	.2	42	20	731	4.01	22	2	<2	12	55	<.2	<.5	<.5	37	1.21	.069	37	28	.65	88	.020	3	1.54	.014	.18	1	<1	4.7	<1<.01	4
01240	.5	33	37	91	.4	41	15	591	3.87	27	2	<2	9	21	.2	.6	<.5	32	.22	.086	34	28	.45	105	.008	3	1.51	.007	.12	2	<1	4.6	<1<.01	3
RE 01240	.6	34	38	93	.4	42	15	609	4.00	26	2	<2	9	22	<.2	<.5	<.5	32	.23	.087	36	28	.46	106	.008	2	1.56	.008	.12	2	<1	4.9	1<.01	3
01241	.8	19	22	57	.3	16	6	287	3.30	22	1	<2	2	10	<.2	.7	<.5	44	.08	.076	24	16	.12	60	.014	<1	.70	.004	.05	2	<1	.9	<1 .01	4
01242	.8	17	17	43	.3	14	4	346	2.62	23	<1	<2	1	6	<.2	<.5	<.5	40	.04	.060	26	12	.08	39	.014	<1	.54	.003	.04	2	<1	.8	1<.01	4
01243	.4	30	24	68	.3	28	11	387	3.43	33	1	<2	4	18	<.2	1.4	.7	24	.18	.054	29	20	.31	95	.005	<1	1.12	.006	.10	2	<1	2.2	1<.01	2
01244	.3	34	33	81	.2	37	20	1057	3.98	21	2	<2	7	17	<.2	<.5	<.5	37	.25	.071	37	29	.63	75	.014	3	1.52	.006	.08	1	<1	4.0	1 .01	4
01245	.4	14	14	35	.2	12	4	144	2.33	19	1	<2	3	7	<.2	<.5	<.5	24	.06	.034	29	13	.17	56	.009	1	.68	.003	.05	1	<1	1.1	<1<.01	3
01246	.5	17	20	43	.5	15	5	181	3.14	25	1	<2	2	7	<.2	<.5	<.5	24	.08	.051	20	16	.15	55	.006	<1	.74	.003	.05	2	<1	.9	<1 .02	2
01247	.3	26	19	55	.2	26	10	360	2.98	26	2	<2	5	9	<.2	.5	<.5	22	.07	.045	31	17	.28	54	.006	2	.98	.004	.06	2	<1	2.1	1<.01	2
01248	.4	26	21	57	.6	29	10	590	3.42	29	2	<2	6	13	<.2	<.5	<.5	26	.18	.053	32	20	.31	62	.005	1	1.17	.005	.08	1	<1	2.9	<1<.01	3
01249	.6	9	17	19	.3	7	2	60	1.94	20	<1	<2	1	6	<.2	<.5	<.5	33	.04	.046	26	11	.06	44	.005	1	.69	.003	.04	1	<1	.5	<1 .01	3
01250	.6	14	13	35	.3	12	4	234	2.69	20	<1	<2	4	7	<.2	<.5	<.5	20	.04	.068	27	12	.13	59	.007	<1	.63	.003	.04	1	<1	1.0	<1<.01	3
01251	.4	19	24	47	.2	16	5	166	4.10	27	1	<2	6	6	<.2	<.5	<.5	26	.04	.055	29	18	.22	55	.006	1	.93	.004	.06	2	<1	1.3	1 .01	2
01252	.2	31	24	74	.5	34	11	1068	3.51	28	2	<2	5	19	.2	<.5	<.5	24	.25	.063	31	21	.32	101	.006	1	1.23	.006	.11	1	<1	3.1	1 .02	2
STANDARD C3	27.8	69	36	176	5.5	36	12	814	3.44	59	28	2	23	30	23.9	18.1	23.6	87	.61	.098	22	176	.64	169	.088	23	1.87	.046	.18	15	1	5.0	<1 .03	7
STANDARD G-2	1.6	3	4	46	<.1	7	4	561	2.08	<1	3	<2	5	88	<.2	<.5	<.5	45	.72	.103	11	83	.63	258	.133	7	1.06	.143	.56	2	<1	3.0	1<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

Data ___ FA ___

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01254	.6	20	23	57	.4	21	6	191	3.94	38	1	<2	6	7	<.2	.9	.5	25	.03	.102	27	19	.20	62	.006	1	.90	.004	.08	2	<1	1.5	<1	.01	4
01255	.5	19	18	52	.1	18	6	247	4.56	31	1	<2	5	5	<.2	.5	<.5	27	.04	.092	21	20	.17	49	.008	<1	.96	.003	.04	2	<1	1.2	<1	.02	5
01256	.7	24	27	63	.2	21	8	447	4.45	35	1	<2	2	7	<.2	<.5	<.5	33	.04	.129	23	19	.16	84	.009	<1	.92	.001	.06	2	<1	1.3	<1	.01	6
01257	.4	46	42	110	.5	40	21	2517	5.13	44	4	<2	4	35	.2	<.5	1.3	30	.47	.134	25	27	.24	141	.007	1	1.63	.006	.14	2	<1	3.6	<1	.03	6
01258	<.2	56	47	103	1.3	46	19	2099	4.43	39	5	<2	4	57	.4	<.5	1.0	23	.81	.157	23	26	.29	149	.006	3	1.66	.007	.16	1	<1	4.5	<1	.06	5
01259	.2	32	31	70	.4	30	17	590	3.90	42	3	<2	5	20	<.2	<.5	.7	19	.25	.067	27	17	.28	62	.006	<1	.99	.003	.08	1	<1	2.2	<1	.01	4
01260	.2	30	27	76	.8	28	12	586	3.56	34	3	<2	4	28	<.2	<.5	1.1	18	.35	.095	24	18	.28	88	.005	<1	1.17	.004	.11	1	<1	2.6	<1	.02	4
01261	.2	16	17	47	.4	13	5	195	2.30	23	1	<2	3	15	<.2	<.5	<.5	22	.17	.040	26	14	.17	64	.006	<1	.89	.002	.07	1	<1	1.3	<1	.01	4
01262	<.2	52	38	87	.7	35	18	881	4.12	39	4	<2	6	20	.2	<.5	.8	23	.24	.065	32	24	.28	101	.005	<1	1.45	.005	.11	1	<1	3.0	<1	.02	5
01263	.2	28	27	63	.2	25	13	529	3.48	38	2	<2	6	16	<.2	<.5	.5	16	.17	.058	33	17	.26	56	.004	2	1.02	.001	.06	1	<1	1.8	1	.01	3
01264	<.2	54	30	91	.9	57	15	324	3.91	28	10	<2	9	42	<.2	<.5	<.5	22	.53	.124	55	29	.47	90	.003	<1	2.01	.005	.10	1	<1	5.2	<1	.05	5
01265	<.2	54	31	83	.6	45	16	181	3.09	20	7	<2	8	34	<.2	<.5	<.5	31	.43	.094	40	22	.47	73	.004	<1	1.63	.003	.06	1	<1	4.6	<1	.06	4
01266	<.2	20	16	58	.1	25	10	202	3.83	28	1	<2	6	8	<.2	<.5	<.5	24	.07	.033	27	22	.43	60	.004	<1	1.28	.002	.06	1	<1	1.4	<1	.01	4
01267	<.2	30	24	78	.1	25	10	399	3.97	34	2	<2	3	7	<.2	.6	<.5	29	.06	.047	24	22	.20	91	.006	2	1.28	.002	.08	2	<1	1.6	<1	.02	4
01268	.2	37	31	77	.2	32	14	462	4.17	29	3	<2	6	19	<.2	<.5	<.5	23	.22	.067	43	21	.20	103	.005	<1	1.42	.004	.11	2	<1	2.5	<1	.02	4
01271	.2	4	7	11	<.1	3	1	47	.52	6	<1	<2	2	4	<.2	<.5	<.5	7	.04	.027	28	5	.04	26	.004	<1	.51	<.001	.03	1	<1	.5	<1	<.01	3
01272	.4	18	9	58	.1	20	5	222	3.10	90	1	<2	5	5	<.2	<.5	<.5	28	.03	.055	35	7	.03	23	.005	<1	.59	.001	.03	2	<1	.9	<1	<.01	4
01273	.2	33	28	91	.3	38	18	1858	4.22	40	4	<2	5	26	.2	.5	<.5	20	.36	.133	32	23	.23	91	.006	1	1.69	.005	.06	1	<1	2.3	<1	.05	4
01274	.6	15	7	39	<.1	13	4	237	2.34	23	<1	<2	4	4	<.2	<.5	<.5	23	.05	.037	28	8	.03	33	.005	1	.62	.001	.03	1	<1	1.0	<1	<.01	4
01275	.5	19	31	21	<.1	11	4	93	1.44	21	<1	<2	4	3	<.2	.6	<.5	20	.05	.027	32	4	.02	13	.004	1	.50	<.001	.02	1	<1	.6	<1	<.01	4
01276	.4	33	18	74	.1	23	10	232	4.29	41	1	<2	7	4	<.2	.6	.5	19	.02	.079	42	7	.03	22	.003	1	.65	.001	.04	1	<1	.9	1	.01	3
01277	.3	29	18	50	.4	22	7	228	4.96	78	1	<2	8	5	<.2	<.5	.5	12	.04	.065	35	9	.06	22	.003	<1	.65	<.001	.03	2	<1	1.8	<1	.02	4
01278	<.2	14	16	20	.1	7	3	81	2.01	9	<1	<2	9	2	<.2	<.5	.6	7	.02	.030	50	5	.04	32	.001	<1	.93	<.001	.03	1	<1	.8	<1	<.01	3
RE 01278	<.2	15	15	19	.1	6	2	79	1.99	9	<1	<2	9	3	<.2	<.5	.6	9	.02	.030	50	5	.04	32	.001	<1	.93	<.001	.03	1	<1	.8	1	<.01	3
01279	.4	14	10	38	.1	17	7	108	2.45	10	<1	<2	11	5	<.2	<.5	<.5	29	.01	.045	62	7	.07	21	.002	<1	.91	.001	.03	1	<1	.9	<1	<.01	5
01282	3.3	8	5	24	.1	6	1	63	.76	3	<1	<2	4	4	<.2	<.5	<.5	13	.04	.022	38	4	.02	22	.002	3	.39	.001	.02	<1	<1	.6	<1	<.01	3
01283	.2	22	11	65	.3	16	6	113	2.69	17	2	<2	4	10	.2	<.5	<.5	24	.12	.036	35	15	.17	70	.006	<1	1.23	.001	.04	1	<1	1.4	<1	.01	3
01284	<.2	41	21	72	.2	35	16	709	3.66	24	3	<2	7	16	<.2	<.5	<.5	22	.20	.057	47	22	.41	80	.005	<1	1.44	.003	.07	2	<1	2.8	<1	.02	3
01285	.3	89	37	85	.6	55	19	1729	3.82	23	10	<2	5	48	.6	<.5	.6	24	.70	.178	104	27	.29	116	.011	3	1.98	.005	.08	2	<1	4.4	<1	.07	4
01286	.2	57	26	90	.4	48	17	901	3.71	26	13	<2	6	41	<.2	<.5	<.5	18	.60	.100	54	21	.33	79	.007	1	1.44	.003	.07	1	<1	3.2	<1	.04	3
01287	.4	33	23	72	.3	31	14	642	3.38	31	4	<2	4	32	<.2	<.5	<.5	22	.42	.068	35	21	.32	74	.008	2	1.15	.003	.07	1	<1	2.5	<1	.03	3
01289	<.2	52	23	83	.1	50	23	930	4.35	32	5	<2	11	22	<.2	<.5	<.5	22	.27	.063	41	25	.48	82	.011	2	1.41	.008	.12	1	<1	3.7	<1	<.01	4
01290	.3	26	24	58	.1	18	9	330	2.82	23	2	<2	2	14	<.2	<.5	<.5	28	.18	.056	31	18	.22	79	.008	2	1.06	.003	.07	1	<1	1.4	<1	.01	3
01291	<.2	35	28	86	.3	32	15	548	3.84	28	3	<2	7	20	<.2	<.5	<.5	27	.22	.085	31	26	.38	112	.005	1	1.75	.004	.10	1	<1	3.0	<1	.02	3
STANDARD C3	27.5	67	35	170	5.3	36	11	780	3.29	61	27	2	23	28	22.7	18.1	23.4	79	.58	.096	21	174	.60	161	.081	24	1.84	.040	.16	15	1	4.5	<1	.03	7
STANDARD G-2	1.5	2	3	46	<.1	7	4	544	2.03	<1	4	<2	4	80	<.2	<.5	<.5	41	.67	.104	10	80	.61	248	.126	<1	1.03	.115	.52	2	<1	2.7	<1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01292	.4	9	11	22	.2	8	2	132	1.91	19	<1	<2	3	4	.3	<.5	<.5	13	.04	.070	24	10	.11	34	.003	2	.57	.002	.04	2	<1	.6	<1	.02	3
01293	.4	16	17	39	.1	12	4	162	3.17	30	1	<2	4	5	.2	<.5	.5	13	.06	.051	25	13	.13	46	.004	2	.66	.002	.05	2	<1	.7	1	.01	3
01294	.3	17	17	46	.2	14	5	172	3.19	36	1	<2	7	5	.2	<.5	.8	16	.04	.046	33	15	.22	51	.003	2	.88	.002	.07	2	<1	1.1	<1	.01	3
01295	.5	23	23	55	.2	18	7	277	3.29	34	1	<2	5	7	.2	<.5	.6	22	.06	.042	30	17	.21	89	.005	2	1.08	.003	.10	2	<1	1.5	<1	.01	4
01296	.3	48	30	83	.5	35	16	733	4.13	40	5	<2	6	30	.4	.5	.7	20	.30	.099	28	23	.27	99	.004	1	1.35	.005	.11	1	<1	3.4	<1	.03	4
01297	.3	33	28	67	.7	23	12	496	3.48	34	3	<2	4	33	.3	<.5	.8	19	.39	.085	28	17	.22	79	.005	1	1.00	.004	.09	1	<1	2.2	<1	.03	4
01298	.3	38	30	82	.6	37	16	662	4.27	38	3	<2	5	28	.3	<.5	.8	25	.32	.081	29	24	.33	104	.006	2	1.34	.005	.14	1	<1	3.2	<1	.02	5
01299	.4	28	26	69	.3	25	12	507	3.41	30	2	<2	3	24	.3	1.0	.5	25	.26	.054	28	19	.25	73	.006	1	.92	.002	.07	1	<1	1.8	<1	.01	4
01401	.6	28	23	58	.2	21	7	426	3.63	29	2	<2	2	22	.3	.8	<.5	28	.29	.075	27	15	.13	59	.009	<1	.66	.002	.06	1	<1	1.0	1	.01	4
01402	.3	17	14	50	.2	20	8	345	3.43	31	1	<2	3	14	<.2	<.5	<.5	24	.16	.059	26	20	.31	53	.005	<1	1.13	.002	.05	1	<1	1.2	<1	.01	4
01404	.3	21	20	55	.1	19	7	208	3.30	27	1	<2	5	6	.3	<.5	<.5	19	.05	.038	29	17	.21	65	.005	1	.89	.001	.06	2	<1	1.4	<1	<.01	3
01405	.3	20	18	42	.2	16	5	138	2.47	20	1	<2	4	7	.2	<.5	<.5	21	.07	.034	29	13	.14	98	.005	<1	.88	.001	.06	1	<1	1.3	<1	.01	3
01406	.4	30	25	64	.1	30	12	403	3.48	32	1	<2	6	8	.3	<.5	<.5	21	.07	.036	31	20	.27	99	.005	2	1.04	.003	.10	2	<1	2.0	1	<.01	3
01407	<.2	22	21	51	.3	19	7	231	2.91	23	1	<2	5	10	<.2	<.5	<.5	23	.11	.039	26	16	.20	67	.004	2	1.01	.002	.07	1	<1	1.6	<1	.01	3
01408	.5	34	37	87	.6	26	15	1325	4.16	34	3	<2	3	17	.3	.6	<.5	32	.21	.101	21	26	.22	135	.007	1	1.27	.003	.09	1	<1	2.1	<1	.03	5
RE 01408	.4	34	37	89	.6	26	15	1327	4.22	34	3	<2	3	17	.2	<.5	<.5	31	.22	.104	21	26	.23	138	.007	1	1.30	.003	.10	1	<1	2.2	<1	.03	5
01409	.7	13	12	22	.1	8	2	76	1.27	20	1	<2	1	7	.3	<.5	<.5	20	.09	.024	29	7	.04	40	.005	<1	.41	<.001	.03	1	<1	.5	<1	<.01	3
01410	.3	12	16	35	.1	11	4	163	2.38	18	1	<2	3	6	.2	<.5	<.5	22	.06	.037	26	12	.13	49	.006	1	.68	<.001	.04	1	<1	.9	1	<.01	3
01411	.3	27	19	69	.3	33	12	322	3.65	258	2	<2	5	9	.2	<.5	<.5	27	.09	.050	32	26	.39	68	.006	2	1.36	.002	.07	2	<1	2.3	<1	.01	4
01412	.4	37	21	65	1.1	38	13	598	3.44	166	2	<2	3	25	.4	<.5	<.5	26	.43	.063	41	23	.36	82	.007	2	1.29	.004	.10	1	<1	3.1	<1	.02	4
01413	<.2	20	19	52	<.1	19	7	183	3.02	26	1	<2	5	5	.2	<.5	<.5	24	.05	.031	31	18	.25	75	.006	1	.97	.001	.07	2	<1	1.6	1	<.01	3
01414	<.2	29	20	62	.3	29	13	424	3.30	36	2	<2	6	11	.2	<.5	<.5	24	.14	.048	32	21	.41	68	.006	<1	1.19	.002	.07	1	<1	2.4	<1	<.01	3
01415	.2	35	24	70	.3	36	15	640	3.56	52	2	<2	5	13	.2	<.5	<.5	26	.20	.053	32	22	.41	69	.008	2	1.17	.002	.08	3	<1	3.0	1	.01	3
01416	.5	31	31	100	.4	35	14	556	4.35	39	2	<2	4	12	.2	.7	<.5	30	.11	.076	26	27	.34	102	.009	2	1.28	.003	.10	3	<1	1.9	1	.02	4
01417	.2	27	20	75	<.1	28	11	363	3.61	28	1	<2	6	7	.2	<.5	<.5	28	.05	.054	29	27	.43	79	.012	1	1.34	.002	.09	2	<1	2.1	<1	<.01	3
01418	.2	15	18	51	.1	15	6	251	3.22	26	1	<2	3	7	.2	<.5	<.5	23	.05	.056	25	20	.25	65	.006	<1	.97	<.001	.07	1	<1	1.1	<1	.01	3
01419	<.2	30	21	70	.4	30	14	734	3.76	65	2	<2	6	8	<.2	.5	<.5	28	.07	.072	29	25	.40	83	.006	2	1.48	.002	.09	2	<1	2.8	2	.02	4
01420	<.2	13	15	49	.2	18	6	180	3.22	21	1	<2	3	7	.2	<.5	<.5	32	.09	.054	25	24	.36	77	.010	1	1.12	.001	.05	1	<1	1.3	1	.01	4
01421	<.2	19	17	52	.1	20	8	238	3.31	22	1	<2	7	7	<.2	<.5	<.5	32	.08	.048	31	25	.36	68	.010	1	1.32	.001	.06	1	<1	1.9	1	<.01	4
01422	<.2	25	20	58	.2	24	10	363	3.59	30	1	<2	6	10	<.2	<.5	<.5	29	.09	.047	32	24	.37	62	.005	2	1.40	.002	.07	1	<1	2.3	1	<.01	4
01423	<.2	34	28	74	.3	38	16	455	4.15	36	2	<2	6	15	<.2	<.5	<.5	27	.21	.058	33	27	.46	70	.005	<1	1.59	.003	.09	1	<1	3.0	1	.01	4
01424	<.2	37	33	77	.8	46	17	704	4.03	37	3	<2	8	19	.3	<.5	<.5	24	.30	.059	37	26	.47	77	.005	1	1.57	.003	.09	1	<1	4.0	1	.02	3
01425	.2	40	27	74	.6	39	15	562	3.91	35	3	<2	5	27	.3	<.5	<.5	26	.46	.070	32	24	.37	66	.005	<1	1.36	.003	.08	1	<1	2.9	<1	.02	3
01426	<.2	29	21	68	.4	33	13	475	3.53	32	2	<2	6	15	.2	<.5	<.5	21	.25	.065	31	20	.40	47	.005	1	1.09	.001	.06	2	<1	2.6	<1	.01	2
STANDARD C3	27.3	68	36	173	5.5	36	12	800	3.36	59	26	3	23	30	24.4	17.3	23.3	81	.60	.097	21	174	.63	162	.086	24	1.81	.041	.17	14	1	4.6	<1	.03	7
STANDARD G-2	1.7	3	3	45	<.1	7	4	552	2.05	<1	4	<2	5	85	.2	<.5	<.5	42	.70	.103	10	83	.63	253	.126	1	1.04	.135	.54	2	<1	2.8	1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01428	.4	39	29	49	1.1	35	12	957	2.23	23	3	<2	4	45	.3	<.5	.6	18	.85	.108	35	21	.38	66	.006	3	1.23	.007	.08	1	<1	3.2	<1	.08	4
01429	1.4	36	46	70	.9	41	14	492	3.86	117	3	<2	4	26	.2	<.5	1.2	21	.40	.099	27	26	.33	77	.004	2	1.35	.006	.11	1	<1	2.9	<1	.04	4
01430	1.0	40	35	66	.2	34	15	520	4.98	63	2	<2	6	10	.2	.5	.6	30	.11	.063	28	24	.33	71	.005	1	1.40	.003	.08	2	<1	2.2	<1	.02	6
01431	.4	15	17	43	.3	11	6	480	3.70	25	1	<2	2	5	<.2	<.5	<.5	25	.06	.086	23	18	.18	53	.006	<1	.93	.002	.05	2	<1	.8	<1	.01	4
01433	.4	20	14	47	.4	16	6	394	2.44	21	1	<2	2	11	<.2	<.5	<.5	20	.09	.053	28	15	.21	78	.006	1	.85	.001	.08	2	<1	1.1	1	.01	3
01434	.5	28	23	65	.5	23	10	496	3.36	30	1	<2	2	9	<.2	<.5	.6	22	.06	.074	24	18	.22	106	.005	1	1.06	.004	.11	2	<1	1.2	<1	.02	4
01435	.4	29	25	70	.1	27	11	386	4.54	40	1	<2	6	6	<.2	<.5	.6	23	.04	.078	31	22	.27	74	.006	<1	1.13	.002	.09	2	<1	1.9	1	.01	4
01436	.5	23	20	56	.1	18	7	234	3.89	27	1	<2	3	6	<.2	<.5	.5	21	.06	.058	25	19	.22	50	.006	2	1.03	.001	.05	2	<1	1.0	<1	.01	4
01437	.4	28	20	78	.3	27	11	525	4.13	32	1	<2	4	14	<.2	<.5	<.5	25	.17	.059	30	21	.30	58	.008	<1	1.05	.002	.07	2	<1	1.6	<1	.01	4
01438	.4	7	6	14	.1	4	2	96	.74	6	1	<2	1	14	<.2	<.5	<.5	12	.19	.025	30	6	.05	44	.005	<1	.38	.001	.03	<1	<1	.5	<1	<.01	3
01439	.3	27	18	61	.3	22	9	667	3.37	22	2	<2	3	23	<.2	<.5	<.5	25	.27	.086	35	20	.33	63	.006	1	1.11	.001	.06	1	<1	1.7	<1	.02	4
01440	.3	48	27	72	.3	33	14	638	3.93	28	3	<2	4	33	.2	<.5	<.5	27	.41	.070	36	22	.30	93	.007	<1	1.16	.003	.08	1	<1	2.1	<1	.02	5
RE 01440	.3	48	26	72	.3	33	14	619	3.90	29	3	<2	4	33	.2	<.5	<.5	27	.40	.070	36	23	.30	93	.006	2	1.16	.003	.08	1	<1	2.1	<1	.02	4
01441	<.2	29	26	78	.5	28	13	620	3.30	20	5	<2	5	52	<.2	<.5	<.5	21	.70	.119	37	21	.36	84	.005	<1	1.28	.002	.07	1	<1	2.9	<1	.04	4
01443	.3	34	27	89	.4	33	15	647	3.68	22	4	<2	6	35	.2	.5	<.5	25	.48	.080	33	25	.45	74	.007	<1	1.30	.002	.07	1	<1	3.0	<1	.02	4
01444	.4	59	24	83	.7	43	15	952	3.68	23	9	<2	5	62	.4	<.5	.5	23	.88	.187	52	26	.34	92	.009	<1	1.59	.004	.08	1	<1	3.9	<1	.08	4
01446	.4	19	19	56	.3	21	11	315	3.11	27	2	<2	6	18	<.2	<.5	<.5	18	.24	.047	33	16	.27	62	.004	<1	.91	<.001	.06	1	<1	1.6	<1	.01	3
01447	.4	26	26	70	.2	26	14	428	3.55	34	2	<2	7	17	<.2	<.5	.5	20	.23	.047	38	20	.28	80	.005	<1	1.05	.002	.08	2	<1	2.1	<1	<.01	3
01448	.6	36	29	100	.4	46	15	400	4.99	36	3	<2	7	23	.2	<.5	<.5	29	.33	.059	34	32	.39	139	.004	2	1.82	.004	.12	1	<1	2.9	<1	.02	6
01449	.3	28	22	75	.2	27	10	283	4.53	26	1	<2	8	7	<.2	<.5	<.5	28	.08	.049	37	30	.42	77	.005	<1	1.59	.001	.08	2	<1	2.1	1	.01	5
01450	.4	15	18	67	.1	17	9	296	3.49	19	1	<2	6	7	<.2	<.5	<.5	29	.06	.039	32	22	.31	62	.006	<1	1.35	.001	.05	2	<1	1.4	<1	.01	4
01451	.4	13	33	74	.1	20	9	305	3.43	14	1	<2	7	10	<.2	<.5	<.5	26	.10	.059	25	21	.32	79	.005	<1	1.40	.002	.06	1	<1	1.6	<1	.02	4
01452	.5	22	24	60	.1	22	8	217	3.88	18	1	<2	6	6	<.2	<.5	<.5	22	.03	.053	39	12	.13	64	.005	<1	.89	.001	.05	2	<1	1.1	1	.01	3
01455	.4	8	8	22	.1	6	2	65	1.12	18	<1	<2	4	4	<.2	<.5	<.5	15	.03	.027	33	5	.02	18	.003	<1	.55	<.001	.02	1	<1	.6	<1	<.01	3
01456	.3	2	3	8	.1	2	1	39	.38	2	<1	<2	4	8	<.2	<.5	<.5	8	.03	.021	34	3	.01	18	.003	<1	.44	<.001	.02	1	<1	.5	<1	<.01	4
01458	.5	4	2	14	<.1	4	1	81	.69	6	<1	<2	5	4	<.2	<.5	<.5	18	.04	.016	31	6	.04	18	.003	<1	.73	<.001	.03	1	<1	.6	<1	<.01	5
01459	.6	20	6	68	.1	17	7	154	3.03	25	1	<2	4	11	<.2	<.5	<.5	25	.16	.037	28	10	.06	63	.004	<1	.64	.003	.04	1	<1	1.1	<1	.01	3
01460	.3	21	19	72	.2	31	15	434	3.63	29	2	<2	7	17	<.2	<.5	<.5	19	.21	.066	29	22	.42	80	.004	<1	1.45	.001	.06	1	<1	1.9	<1	.02	4
01461	.5	17	28	55	.3	14	6	162	2.56	13	1	<2	1	7	<.2	<.5	<.5	28	.05	.047	28	12	.04	77	.010	<1	.67	<.001	.04	1	<1	.7	<1	.02	3
01462	.9	11	5	28	.1	9	2	93	1.75	29	<1	<2	3	4	<.2	<.5	<.5	34	.05	.023	36	7	.02	13	.010	<1	.41	<.001	.01	1	<1	.6	<1	<.01	4
01463	.3	3	7	7	.1	2	1	205	.48	7	<1	<2	1	4	<.2	<.5	<.5	10	.03	.031	30	4	.01	31	.003	<1	.34	<.001	.02	<1	<1	.3	<1	<.01	3
STANDARD C3	27.9	70	36	179	5.6	38	12	826	3.47	59	27	3	23	32	23.9	16.3	24.1	85	.61	.095	22	177	.64	170	.090	22	1.85	.045	.18	15	1	4.8	<1	.03	7
STANDARD G-2	1.7	3	2	47	<.1	8	4	568	2.11	<1	3	<2	5	77	<.2	<.5	<.5	44	.69	.107	10	84	.64	242	.135	<1	.93	.082	.50	2	<1	2.8	<1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004381R

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: K. Ross

SAMPLE#	Au* ppb
00258	21.3
00260	47.0
00261	11.9
00262	14.1
00263	10.9
00264	31.0
00265	50.7
00266	13.8
00267	44.9
00268	8.5
00269	298.2
00270	5.9
00271	16.2
00272	177.4
RE 00272	8.5
00274	3.3
00275	16.7
00276	12.3
00277	3.1
00278	243.0
00279	3.0
00280	7.6
00281	1.6
00282	6.9
00283	13.4
00284	3.5
00285	15.4
00286	2.7
00287	1.2
00288	11.3
00289	2.3
00290	11.9
00291	13.3
00292	4.4
STANDARD DS2	194.1

AU* BY ACID LEACHED, ANALYSIS BY ICP/MS. (10 gm)
- SAMPLE TYPE: SOIL PULP
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: NOV 23 2000 DATE REPORT MAILED: Nov 27/00 SIGNED BY ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data___ FA ___

SAMPLE#	Au* ppb
00293	3.8
00294	5.3
00295	2.5
00296	44.2
00298	20.2
00299	5.0
00300	2.5
00501	50.3
00502	29.7
00503	133.3
00504	42.4
00505	69.9
00506	35.5
00507	66.3
00508	209.9
00509	127.9
00510	64.9
RE 00510	48.7
00511	17.8
00512	13.8
00513	19.9
00514	85.3
00515	20.9
00516	15.2
00517	5.8
00518	55.1
00519	132.0
00523	85.7
00524	101.2
00525	52.2
00526	21.7
00527	15.1
00528	89.2
00559	13.5
STANDARD DS2	203.8

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA

SAMPLE#	Au* ppb
00560	11.7
00561	78.0
00562	9.2
00564	41.9
00575	2050.0
00576	1969.0
00577	63.6
00578	51.8
00579	120.1
00580	18.6
00581	33.8
00582	660.0
00583	90.1
00585	462.8
00586	24.7
00587	57.8
00588	11.4
00589	32.0
00591	8.3
00592	12.0
RE 00592	4.2
00593	39.1
00594	13.2
00595	8.0
00596	30.0
00597	12.8
00598	23.5
00599	38.1
00600	291.3
00602	5.3
00603	32.5
00604	15.6
00605	110.4
00606	7.8
STANDARD DS2	192.0

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au* ppb
00607	13.1
00608	4.4
00609	89.0
00610	19.8
00611	38.0
00612	5.0
00613	12.8
00614	33.6
00615	6.0
00616	18.3
00617	20.7
00618	7.9
00620	8.8
00621	5.1
00622	7.4
00623	4.6
00624	4.9
00625	3.7
00626	5.2
RE 00626	5.7
00627	3.3
00628	1.4
00629	7.2
00632	23.8
00633	4.4
00634	5.7
00635	10.9
00636	12.7
00637	8.3
00638	5.1
00639	3.0
00640	5.3
00641	28.2
00642	13.9
STANDARD DS2	195.2

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Au* ppb
00643	10.7
00644	6.1
00645	9.9
00646	4.5
00647	.7
00648	.6
00649	6.0
00650	10.6
00651	15.4
00652	15.7
00654	8.9
00655	7.2
00656	27.8
00657	42.3
RE 00657	15.7
00701	17.8
00702	71.3
00703	80.2
00704	93.2
00705	43.5
00707	156.6
00708	56.4
00709	29.8
00710	132.1
00711	36.9
00712	94.3
00713	13.2
00714	200.6
00715	110.4
00716	92.6
00717	19.8
00718	19.7
00719	70.1
00720	68.3
STANDARD DS2	190.0

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data /- FA ___

SAMPLE#	Au* ppb
00721	57.6
00722	11.8
00723	73.0
00724	14.2
00725	55.8
00726	194.0
00727	83.2
00728	13.8
00729	11.5
00730	23.2
00732	40.0
00733	37.7
00734	10.4
00735	54.3
00736	1.6
RE 00736	41.8
00780	23.3
00781	36.8
00782	21.3
00783	1.8
00784	40.4
00785	4.9
00786	81.9
00787	15.8
00788	26.9
00789	293.5
00790	16.5
00791	8.3
00792	14.7
00793	149.7
00794	16.6
00796	28.5
00797	59.1
00798	33.3
STANDARD DS2	192.6

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data___ FA ____

SAMPLE#	Au* ppb
00799	24.4
00800	13.9
00820	233.5
00821	41.4
00822	85.6
00823	33.4
00824	8.2
00825	60.3
00826	15.8
00827	34.4
00828	4.8
00829	4.6
00830	12.2
00831	5.7
00832	10.3
RE 00832	6.2
00833	2.6
00834	7.0
00835	8.3
00836	6.5
01201	56.5
01202	60.5
01203	28.8
01204	62.7
01205	14.9
01206	18.3
01207	23.4
01208	76.9
01209	27.0
01210	49.4
01211	15.1
01212	16.9
01213	163.7
01214	100.6
STANDARD DS2	197.7

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data__ FA ___

SAMPLE#	Au* ppb
01215	225.1
01216	550.7
01218	23.9
01219	17.6
01220	2.1
01221	119.2
01222	26.4
01223	20.7
01224	20.4
01225	14.4
01226	42.9
01227	9.5
01228	12.6
01229	14.1
01232	116.3
01234	138.3
01236	25.0
01237	24.6
01238	8.1
01239	6.3
01240	29.7
RE 01240	78.7
01241	2.9
01242	28.2
01243	124.6
01244	12.8
01245	7.3
01246	40.5
01247	48.7
01248	24.9
01249	7.4
01250	18.6
01251	29.4
01252	34.2
STANDARD DS2	202.9

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Au* ppb
01254	35.6
01255	12.1
01256	24.9
01257	15.1
01258	63.2
01259	81.2
01260	49.5
01261	35.9
01262	43.8
01263	97.2
01264	11.4
01265	6.3
01266	2.2
01267	17.9
01268	62.9
01271	93.0
01272	50.9
01273	15.7
01274	25.1
01275	8.9
01276	4.4
01277	11.4
01278	2.5
RE 01278	15.2
01279	5.9
01282	18.6
01283	41.9
01284	31.0
01285	10.8
01286	30.1
01287	21.3
01289	7.5
01290	13.5
01291	26.4
STANDARD DS2	197.3

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ___

SAMPLE#	Au* ppb
01292	46.5
01293	44.2
01294	78.0
01295	108.9
01296	114.2
01297	34.1
01298	234.6
01299	34.2
01401	15.5
01402	19.6
01404	68.7
01405	24.6
01406	34.9
01407	9.8
01408	20.4
RE 01408	5.5
01409	341.3
01410	15.4
01411	23.4
01412	81.5
01413	133.8
01414	9.8
01415	52.6
01416	12.6
01417	42.4
01418	116.4
01419	15.8
01420	5.8
01421	8.1
01422	11.1
01423	12.6
01424	66.0
01425	18.7
01426	37.0
STANDARD DS2	193.1

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA___

SAMPLE#	Au* ppb
01428	29.3
01429	48.5
01430	43.3
01431	4.6
01433	30.2
01434	27.6
01435	55.1
01436	74.8
01437	59.7
01438	52.0
01439	297.4
01440	4.5
RE 01440	10.8
01441	5.3
01443	4.2
01444	48.9
01446	31.7
01447	37.9
01448	37.3
01449	8.9
01450	2.9
01451	6.3
01452	28.4
01455	11.6
01456	5.0
01458	20.1
01459	9.6
01460	14.5
01461	29.3
01462	16.0
01463	39.1
STANDARD DS2	198.1

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA

ACME LYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. NCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(60 53-1716
9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004434 Page 1

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: R. Hall

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00658	3.7	26	14	59	.6	22	5	124	2.78	17	1	<2	4	10	<.2	1.5	<.5	24	.02	.083	23	17	.21	154	.013	5	.79	.004	.08	1	<1	1.2	<1	.02	3
00659	3.8	25	12	59	.6	22	5	127	2.72	18	2	<2	4	10	<.2	1.4	<.5	24	.02	.094	21	16	.22	153	.012	3	.74	.004	.07	<1	<1	1.1	<1	.02	3
00660	4.0	26	12	64	.7	23	5	128	2.80	18	1	<2	5	10	<.2	1.8	<.5	22	.02	.081	21	16	.23	157	.013	2	.72	.004	.07	<1	<1	1.2	<1	.02	2
00661	1.4	8	8	16	.5	5	1	70	.95	6	<1	<2	1	6	<.2	<.5	<.5	17	.02	.042	26	8	.05	128	.013	4	.46	.003	.06	<1	<1	.4	1	<.01	4
00662	1.2	6	8	16	.5	4	1	57	.78	4	<1	<2	<1	6	<.2	<.5	<.5	13	.03	.048	22	7	.04	108	.007	2	.44	.004	.05	<1	<1	.3	1	.01	4
00664	2.4	16	14	48	.9	15	6	280	2.50	12	1	<2	1	16	<.2	.6	<.5	28	.13	.069	27	17	.26	192	.009	4	1.01	.005	.09	1	<1	1.1	<1	.01	4
00665	2.6	22	18	58	.4	19	6	225	3.32	13	2	<2	7	10	<.2	.9	<.5	29	.06	.162	27	24	.27	212	.010	3	1.32	.005	.10	1	<1	1.9	<1	.01	5
00666	1.4	6	9	17	<.1	5	1	62	1.47	12	<1	<2	2	7	<.2	<.5	<.5	29	.02	.125	31	10	.08	74	.013	<1	.54	.004	.05	1	<1	.7	<1	<.01	5
00667	3.1	24	23	56	.6	22	6	198	3.71	29	2	<2	2	11	<.2	1.1	.5	47	.07	.361	22	19	.20	148	.015	2	.79	.004	.07	<1	<1	1.1	<1	.03	4
00668	1.5	12	15	38	2.7	14	4	155	2.66	15	1	<2	4	10	<.2	.5	<.5	26	.07	.080	23	16	.22	135	.010	1	.77	.004	.06	<1	<1	.9	<1	.02	4
00669	1.2	24	18	52	.6	19	8	237	3.08	15	1	<2	4	11	<.2	.9	<.5	27	.07	.050	26	21	.27	285	.010	4	1.19	.006	.08	<1	<1	1.5	<1	.01	4
00670	.5	47	25	88	<.1	47	22	782	4.00	26	1	<2	14	16	.2	.8	<.5	34	.18	.070	42	28	.59	294	.028	4	1.52	.012	.14	1	1	3.9	<1	<.01	4
RE 00670	.4	47	26	88	<.1	47	22	802	4.16	28	1	<2	13	17	.2	1.0	<.5	32	.18	.070	42	28	.60	296	.027	3	1.53	.011	.13	1	1	4.1	<1	<.01	3
00671	1.2	33	25	86	.2	33	15	415	3.41	21	2	<2	15	15	<.2	1.5	<.5	15	.11	.060	37	12	.22	168	.016	3	.89	.006	.08	<1	<1	2.8	<1	<.01	2
00672	.6	39	24	83	<.1	42	18	684	3.64	19	2	<2	15	20	<.2	.8	<.5	23	.23	.063	37	19	.39	151	.025	2	1.13	.010	.11	<1	1	3.2	<1	<.01	2
00673	.3	29	20	67	<.1	34	15	566	2.98	15	2	<2	15	11	<.2	.8	<.5	13	.13	.055	38	12	.24	105	.017	2	.71	.006	.06	<1	<1	2.1	1	<.01	2
00674	.4	27	20	63	<.1	33	14	573	2.99	12	2	<2	14	13	<.2	.7	<.5	13	.13	.058	39	12	.22	111	.020	2	.68	.005	.06	<1	<1	2.2	1	<.01	1
00675	.7	32	22	74	<.1	37	16	644	3.32	13	2	<2	13	15	<.2	<.5	<.5	21	.18	.063	36	18	.33	132	.030	<1	.93	.008	.08	<1	1	2.8	<1	<.01	2
00677	.9	45	24	103	.2	53	21	886	4.00	36	1	<2	11	25	.3	.8	1.2	26	.30	.082	34	20	.47	69	.019	1	1.09	.009	.10	1	<1	3.3	<1	.01	2
00678	1.4	45	28	117	.3	50	17	586	3.65	56	2	<2	10	21	.4	1.2	1.1	15	.17	.083	30	13	.25	51	.013	2	.71	.006	.07	1	<1	2.6	<1	.01	1
00679	2.2	57	32	164	1.3	66	20	769	4.39	62	3	8	12	25	.6	1.7	1.9	19	.20	.078	30	17	.26	83	.016	2	.98	.009	.12	1	1	3.7	1	<.01	1
00680	2.4	54	32	156	.3	68	21	809	4.39	57	3	<2	11	28	.5	.9	4.4	21	.28	.083	30	18	.29	87	.018	6	1.01	.011	.13	1	<1	3.6	<1	.01	1
00681	2.1	54	31	153	.3	67	20	780	4.27	58	3	<2	11	26	.5	1.5	2.1	21	.25	.080	28	17	.27	87	.018	3	1.00	.010	.13	1	<1	3.6	1	<.01	1
00682	3.0	40	17	67	1.1	33	14	3461	3.04	7	5	<2	2	73	.4	.5	<.5	27	.67	.197	15	29	.27	641	.015	3	1.43	.007	.10	<1	<1	2.9	<1	.08	2
00683	2.8	38	16	61	.5	32	13	3174	2.91	7	5	<2	2	67	.3	.5	<.5	25	.60	.197	17	28	.26	607	.015	3	1.40	.007	.09	<1	<1	2.8	1	.07	2
00684	1.6	17	20	49	.1	17	5	143	3.45	12	1	<2	8	6	<.2	.8	<.5	28	.04	.035	26	16	.25	123	.013	<1	.84	.003	.06	<1	<1	1.3	<1	.01	2
00685	1.4	16	21	47	<.1	16	5	174	3.35	10	1	<2	6	6	<.2	.7	<.5	26	.04	.030	28	17	.24	121	.012	3	.86	.003	.06	<1	<1	1.4	<1	<.01	2
00686	1.7	8	10	26	1.0	7	2	102	2.01	7	<1	<2	4	5	<.2	<.5	<.5	40	.03	.048	22	14	.14	134	.019	3	.67	.003	.05	<1	<1	1.2	<1	<.01	4
00687	1.4	6	10	18	.9	5	1	61	1.50	6	<1	<2	4	5	<.2	<.5	<.5	33	.03	.030	23	11	.12	126	.018	2	.61	.003	.04	<1	<1	1.0	<1	<.01	5
00688	1.7	16	17	42	.4	14	4	122	3.63	10	1	<2	4	6	<.2	1.0	<.5	33	.03	.105	21	18	.15	76	.014	<1	.99	.004	.05	<1	<1	1.3	<1	.02	2
00689	1.2	4	11	16	.1	4	1	163	1.39	7	<1	<2	3	6	<.2	<.5	<.5	27	.03	.134	25	10	.09	80	.014	<1	.51	.003	.05	<1	<1	.7	<1	<.01	5
00690	1.6	5	12	19	.1	5	1	189	1.95	7	<1	<2	5	6	<.2	<.5	<.5	27	.03	.135	25	11	.09	83	.013	3	.57	.003	.04	<1	<1	.9	<1	<.01	3
00691	3.2	21	11	63	.2	19	4	100	2.72	12	1	<2	6	8	<.2	1.3	<.5	20	.02	.060	22	18	.30	193	.012	<1	.95	.003	.08	<1	<1	1.6	<1	.02	1
00692	3.3	25	11	70	.6	22	4	112	2.86	11	1	<2	7	9	<.2	1.4	<.5	20	.03	.074	21	21	.31	196	.012	3	1.15	.003	.08	<1	1	1.7	<1	.02	1
STANDARD C3	27.9	69	37	178	5.7	39	12	806	3.43	56	24	<2	23	30	24.9	18.3	23.2	83	.61	.101	18	178	.64	163	.091	20	1.87	.047	.18	15	2	4.5	<1	.03	6
STANDARD G-2	1.7	4	3	48	<.1	8	4	562	2.13	<1	3	<2	5	92	<.2	<.5	<.5	42	.74	.111	8	82	.64	263	.137	2	1.16	.085	.61	2	1	2.7	<1	<.01	5

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
- SAMPLE TYPE: SOIL SS80 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 31 2000 DATE REPORT MAILED: Nov 14/00 SIGNED BY ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00694	1.8	17	13	42	<.1	12	4	351	2.39	11	<1	<2	1	8	<.2	.7	<.5	26	.05	.049	23	15	.14	249	.010	<1	.65	.004	.07	<1	<1	1.0	<1	<.01	3
00695	.7	23	17	46	.9	22	9	662	3.39	9	19	<2	1	122	<.2	<.5	<.5	17	1.48	.115	11	18	.31	324	.007	2	1.05	.009	.10	<1	1	1.8	<1	.15	2
00696	.4	13	17	66	<.1	15	12	209	2.81	5	2	<2	6	24	<.2	.6	<.5	9	.25	.056	24	6	.09	81	.002	1	.56	.003	.04	<1	<1	1.3	<1	.01	1
00697	.3	16	14	75	<.1	20	11	126	2.89	4	1	<2	10	17	<.2	<.5	.5	7	.18	.039	39	5	.11	63	.001	1	.56	.003	.04	<1	<1	1.2	<1	<.01	1
00698	.6	22	21	67	<.1	26	13	405	2.82	10	2	<2	8	10	<.2	<.5	<.5	12	.09	.051	31	10	.15	105	.003	1	.69	.003	.05	<1	<1	1.6	<1	.01	2
00699	1.1	17	17	56	.4	20	8	493	2.46	8	2	<2	2	44	<.2	<.5	<.5	18	.45	.087	17	15	.21	211	.005	<1	.97	.005	.08	<1	1	1.9	1	.03	3
00700	1.0	19	17	60	.4	21	9	577	2.48	8	3	<2	3	45	<.2	<.5	<.5	18	.46	.084	18	15	.21	206	.006	<1	.97	.006	.08	<1	<1	2.0	<1	.03	3
00839	.7	31	25	73	<.1	46	17	728	3.26	10	2	<2	16	16	<.2	.7	<.5	12	.14	.061	37	11	.21	149	.012	<1	.58	.005	.07	<1	<1	2.3	<1	<.01	1
00840	.9	30	22	72	<.1	33	14	550	2.85	10	2	<2	15	12	.2	.6	<.5	14	.09	.054	42	12	.22	142	.015	2	.63	.004	.06	<1	<1	2.2	<1	<.01	2
00841	.9	31	21	71	<.1	34	13	539	2.93	12	2	<2	15	11	<.2	1.1	<.5	14	.09	.055	38	11	.23	137	.015	1	.64	.003	.06	<1	<1	2.1	<1	<.01	2
00842	.9	34	22	75	.2	34	14	591	3.06	11	2	<2	16	14	<.2	.9	<.5	19	.11	.060	44	13	.26	168	.024	1	.77	.004	.06	<1	<1	2.6	<1	<.01	2
00843	1.7	37	21	84	.3	35	14	524	3.15	12	2	<2	13	18	<.2	1.2	<.5	20	.12	.062	38	16	.29	235	.026	2	1.09	.005	.07	<1	<1	3.6	1	<.01	2
00844	1.6	26	20	74	.2	28	13	598	3.43	20	1	<2	5	10	<.2	.6	.5	29	.06	.067	29	24	.36	334	.009	<1	1.32	.006	.10	<1	1	2.6	<1	.01	3
00845	1.5	23	19	69	.6	27	12	500	3.24	17	1	<2	4	23	<.2	<.5	<.5	28	.17	.074	25	23	.37	466	.008	<1	1.31	.005	.10	1	<1	2.5	<1	.02	3
RE 00845	1.5	24	20	69	.7	28	13	509	3.25	18	2	<2	4	23	<.2	<.5	<.5	30	.18	.078	25	24	.38	485	.008	<1	1.33	.005	.10	<1	1	2.6	<1	.02	3
00846	1.3	25	19	70	.2	30	13	736	3.24	19	2	<2	3	17	.2	<.5	<.5	30	.15	.075	26	23	.38	471	.008	4	1.30	.005	.11	<1	<1	2.5	<1	.02	3
00847	1.1	26	18	62	.3	28	12	746	2.92	18	1	<2	4	19	<.2	<.5	<.5	27	.22	.055	25	19	.34	329	.011	2	1.09	.005	.10	<1	<1	2.4	1	.01	2
00848	.8	6	11	11	.5	4	1	37	1.59	9	<1	<2	<1	12	<.2	<.5	.6	19	.09	.052	19	9	.06	93	.005	2	.47	.003	.04	<1	<1	.4	<1	.02	3
00849	.9	7	10	25	.1	8	3	220	2.09	11	<1	<2	5	5	<.2	<.5	<.5	26	.05	.058	28	13	.14	72	.011	<1	.74	.003	.06	<1	<1	1.1	<1	<.01	4
00850	.5	6	9	12	.3	4	1	76	1.63	8	<1	<2	<1	6	<.2	<.5	<.5	19	.05	.069	20	10	.07	60	.006	1	.59	.003	.04	<1	<1	.5	<1	.01	3
00851	1.4	16	16	49	.6	19	6	188	4.37	21	1	<2	3	12	<.2	.8	<.5	41	.13	.162	24	25	.34	113	.010	1	1.10	.003	.05	1	<1	1.3	<1	.02	4
00852	2.3	28	15	68	.1	28	10	469	2.86	19	2	<2	5	17	<.2	.8	<.5	28	.09	.052	29	19	.31	397	.010	3	.96	.004	.06	<1	<1	2.0	<1	.01	2
00854	2.3	25	13	53	.5	23	9	346	2.54	18	2	<2	4	11	<.2	.7	<.5	25	.06	.045	28	17	.28	277	.010	1	.85	.004	.06	<1	<1	1.9	<1	<.01	2
00855	4.1	25	16	43	.8	15	4	122	3.04	22	2	<2	6	11	<.2	1.6	<.5	38	.05	.076	27	16	.17	196	.015	2	.67	.003	.06	<1	<1	1.5	<1	<.01	2
00857	3.3	37	19	74	.8	39	13	543	2.91	23	4	<2	5	34	.2	1.5	<.5	26	.24	.049	24	19	.31	432	.012	3	.89	.005	.08	<1	<1	2.7	<1	.02	1
00858	4.2	28	13	62	1.7	25	8	274	2.35	17	4	<2	2	28	.2	1.3	<.5	27	.12	.055	21	18	.24	481	.007	2	.87	.004	.08	<1	<1	1.9	<1	.02	2
00860	.6	29	23	89	<.1	32	13	573	2.93	11	2	<2	19	18	<.2	1.6	.5	7	.14	.062	47	6	.11	80	.003	3	.43	.003	.04	<1	<1	2.1	1	<.01	<1
00861	1.1	29	19	76	<.1	29	12	470	2.74	10	2	<2	12	11	<.2	1.1	<.5	12	.06	.040	39	9	.14	78	.010	<1	.50	.002	.04	<1	<1	1.9	<1	<.01	<1
00862	1.4	29	19	75	.1	31	12	516	2.86	9	2	<2	12	18	.2	.8	<.5	17	.14	.048	34	12	.21	134	.015	3	.75	.004	.06	<1	<1	2.7	<1	<.01	1
00863	1.6	35	21	83	.2	35	14	423	3.09	11	2	<2	13	18	.2	.9	<.5	19	.15	.047	34	12	.20	124	.024	6	.78	.005	.06	<1	<1	3.0	<1	<.01	1
00864	.6	32	18	67	<.1	32	13	468	3.09	15	1	<2	11	15	.2	<.5	<.5	26	.18	.042	32	17	.30	119	.029	2	.77	.004	.04	<1	<1	2.8	<1	<.01	1
00865	.8	37	22	74	.1	41	17	908	3.62	20	1	<2	10	24	.2	<.5	<.5	25	.30	.061	29	21	.36	184	.025	<1	.90	.005	.06	<1	1	3.4	<1	.02	<1
00866	1.3	22	23	56	.9	20	13	346	2.91	11	3	<2	4	47	.2	<.5	<.5	20	.40	.077	24	17	.24	614	.004	3	1.10	.005	.08	<1	<1	2.6	<1	.03	2
00867	1.2	16	18	48	.6	18	9	259	2.55	11	1	<2	4	50	<.2	<.5	<.5	23	.50	.057	23	16	.29	723	.003	2	1.10	.006	.07	<1	<1	2.2	<1	.03	2
STANDARD C3	27.9	68	37	172	5.7	38	12	813	3.42	59	24	<2	23	31	25.4	18.6	23.5	87	.62	.098	19	183	.65	165	.093	21	1.82	.047	.19	15	2	4.8	<1	.03	6
STANDARD G-2	1.7	4	3	48	<.1	7	4	586	2.21	<1	2	<2	5	94	<.2	<.5	<.5	46	.77	.105	8	83	.67	260	.138	2	1.12	.086	.62	2	1	3.0	<1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00868	2.1	22	22	66	1.5	25	16	757	3.35	11	5	<2	5	38	<.2	<.5	<.5	19	.38	.086	24	16	.23	505	.004	1	1.02	.004	.07	<1	<1	2.8	1	.03	2
00869	2.4	37	27	45	2.8	25	14	494	2.29	9	11	<2	3	78	.3	<.5	<.5	16	.67	.117	21	16	.23	716	.004	2	1.14	.007	.07	<1	1	2.5	1	.12	2
00870	2.4	12	20	51	2.6	14	6	121	2.32	7	2	<2	4	17	<.2	.7	<.5	22	.10	.069	23	16	.22	426	.005	1	1.10	.004	.07	<1	<1	1.4	<1	.02	4
00871	3.4	22	24	40	3.6	17	17	860	3.03	10	7	<2	3	45	.3	<.5	<.5	20	.26	.124	23	17	.20	764	.005	2	1.17	.004	.08	<1	1	2.1	1	.04	3
00872	2.5	20	18	51	1.3	18	12	458	2.34	10	4	<2	3	13	<.2	<.5	<.5	18	.08	.063	23	15	.21	349	.006	1	1.02	.003	.06	<1	<1	1.5	<1	.02	3
00873	1.1	23	18	50	.3	21	11	342	2.56	12	2	<2	4	14	<.2	<.5	<.5	23	.10	.040	27	17	.28	238	.010	<1	1.03	.004	.07	<1	<1	1.4	<1	.01	4
00874	2.6	14	11	38	.8	13	5	244	1.83	9	1	<2	2	26	<.2	<.5	<.5	24	.16	.043	21	14	.19	424	.007	1	.76	.004	.06	<1	<1	.7	1	.01	4
00876	3.2	25	11	35	.9	16	4	165	1.80	11	2	<2	2	28	.2	<.5	<.5	21	.15	.039	24	13	.13	434	.009	1	.61	.003	.05	<1	<1	.9	1	.01	3
00877	1.7	9	10	19	.7	6	1	75	1.62	10	<1	<2	2	12	<.2	<.5	<.5	25	.06	.133	24	12	.08	183	.012	<1	.55	.002	.05	<1	<1	.7	<1	<.01	4
00878	1.9	19	14	53	.8	22	7	157	4.05	18	1	<2	9	7	<.2	<.5	<.5	29	.07	.189	28	25	.35	102	.010	<1	1.15	.003	.06	<1	<1	1.6	<1	.01	4
00879	2.8	10	16	22	1.1	7	2	170	2.68	11	<1	<2	3	7	<.2	.5	<.5	31	.02	.201	20	17	.10	108	.012	<1	.67	.002	.04	<1	<1	.7	<1	.01	3
00880	.4	2	3	6	.4	1	<1	111	.14	<1	<1	<2	2	7	<.2	<.5	<.5	4	.03	.014	29	4	.01	122	.005	<1	.19	.002	.02	<1	<1	.2	<1	<.01	4
00881	4.9	29	12	72	1.0	27	5	324	2.63	18	1	<2	2	16	.2	1.0	<.5	27	.04	.066	20	21	.29	292	.011	1	.89	.003	.09	<1	<1	1.2	<1	.02	3
00882	3.5	20	16	53	2.0	19	5	219	3.06	20	1	<2	4	11	<.2	.9	<.5	27	.06	.108	24	17	.21	169	.013	<1	.76	.003	.06	1	<1	1.2	<1	.01	3
01001	.9	9	15	29	<.1	8	3	95	2.15	8	<1	<2	3	14	<.2	<.5	<.5	33	.11	.042	24	11	.12	140	.012	<1	.73	.004	.05	<1	<1	.8	<1	.01	4
01002	.7	6	13	21	<.1	6	2	114	1.51	9	<1	<2	1	5	<.2	<.5	<.5	32	.03	.033	22	12	.10	81	.010	<1	.64	.003	.04	<1	<1	.6	<1	.01	5
01003	.8	18	23	59	.4	19	8	250	3.83	14	1	<2	2	11	<.2	.8	<.5	37	.10	.058	29	24	.26	215	.013	<1	1.19	.004	.06	<1	<1	1.7	<1	.02	4
01004	.8	21	24	67	.7	22	8	267	3.97	14	1	<2	2	15	<.2	.5	<.5	35	.13	.061	27	25	.27	228	.012	1	1.24	.004	.07	<1	<1	1.6	<1	.02	3
01005	.6	38	28	88	<.1	42	19	730	3.71	18	1	<2	10	23	.2	<.5	<.5	28	.34	.072	33	21	.47	101	.022	<1	1.13	.005	.08	<1	1	3.5	1	<.01	2
RE 01005	.6	40	29	91	<.1	43	19	754	3.74	19	1	<2	12	24	<.2	.5	<.5	26	.34	.074	35	22	.48	106	.023	<1	1.16	.005	.08	<1	<1	3.6	1	<.01	2
01006	.8	36	25	82	<.1	37	16	582	3.46	19	1	<2	7	22	.3	<.5	<.5	28	.30	.066	33	21	.45	107	.018	<1	1.16	.005	.07	<1	1	2.9	<1	<.01	3
01007	.6	34	25	77	.1	35	16	612	3.23	19	1	<2	6	23	.3	<.5	<.5	26	.30	.063	30	20	.41	100	.017	2	1.08	.005	.07	<1	<1	2.7	<1	<.01	2
01008	1.0	38	23	88	.1	41	17	620	3.30	12	1	<2	12	35	.3	<.5	<.5	19	.49	.056	31	16	.36	106	.018	<1	.95	.004	.05	<1	<1	2.7	2	<.01	2
01009	1.1	36	23	90	.1	42	18	839	3.25	9	2	<2	12	17	.2	<.5	<.5	17	.17	.057	31	16	.31	127	.020	<1	.89	.003	.05	<1	1	2.4	1	<.01	1
01010	.9	36	22	83	.6	38	16	612	3.19	12	1	10	11	30	.3	<.5	<.5	21	.38	.053	30	17	.37	105	.020	<1	.93	.004	.06	<1	<1	2.7	<1	<.01	2
01011	.9	35	22	82	.1	37	16	605	3.16	12	1	<2	12	46	.2	<.5	<.5	21	.66	.056	33	17	.38	102	.022	<1	.95	.004	.06	<1	<1	2.8	<1	<.01	2
01300	3.6	18	13	53	1.1	18	5	224	2.42	16	2	<2	3	12	.2	.8	<.5	23	.05	.044	22	14	.20	271	.007	<1	.76	.002	.05	<1	<1	1.0	<1	.01	3
01301	4.0	22	15	65	.2	21	6	223	3.20	19	2	<2	3	13	.2	1.1	.5	30	.06	.066	23	18	.23	201	.012	2	.83	.003	.06	<1	<1	1.2	<1	.01	2
01302	4.2	18	19	36	.4	12	2	141	3.36	20	1	<2	7	9	<.2	.9	.5	40	.03	.090	23	17	.12	106	.013	1	.77	.003	.06	<1	<1	1.2	<1	.01	2
01303	3.2	20	17	44	4.2	14	4	376	3.21	15	1	<2	4	11	<.2	.8	.5	27	.09	.123	21	17	.13	106	.011	<1	.77	.004	.07	<1	<1	1.0	<1	.01	2
01304	3.3	22	21	55	.4	19	6	580	3.63	19	2	<2	1	8	.2	.9	<.5	37	.03	.138	21	19	.18	184	.010	<1	.92	.004	.08	<1	<1	.8	1	.02	2
01305	1.2	23	18	64	.7	27	12	880	2.76	14	2	<2	4	20	.2	<.5	<.5	24	.14	.063	25	18	.35	288	.009	2	1.05	.004	.08	<1	<1	1.8	1	.02	2
01306	1.4	33	24	89	3.2	54	14	1060	3.25	15	7	<2	3	53	.7	<.5	<.5	27	.49	.090	27	24	.43	784	.008	1	1.41	.005	.10	<1	1	3.1	2	.03	2
01307	.9	14	17	56	.1	20	9	303	2.98	14	1	<2	4	9	<.2	<.5	<.5	29	.07	.053	26	18	.33	225	.008	1	1.09	.004	.08	<1	<1	1.4	<1	.01	3
STANDARD C3	27.6	67	35	176	5.6	39	12	781	3.33	58	24	<2	22	31	24.8	16.1	23.6	85	.59	.100	19	178	.63	166	.092	19	1.81	.042	.17	14	2	4.4	1	.03	6
STANDARD G-2	1.6	4	2	47	<.1	8	4	561	2.11	<1	2	<2	5	77	<.2	<.5	<.5	46	.69	.108	8	81	.64	243	.137	3	.97	.085	.53	2	<1	2.7	<1	<.01	6

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01308	1.0	24	21	69	.3	31	14	366	3.79	19	1	<2	6	18	.2	.8	<.5	30	.15	.057	29	28	.50	302	.007	3	1.55	.007	.10	1	1	2.1	<1	.01	4
01309	.7	35	18	67	.1	32	13	405	3.16	17	1	<2	6	9	.2	.7	<.5	29	.08	.048	38	23	.43	224	.012	6	1.26	.007	.10	1	<1	2.6	<1	.01	4
01310	1.0	23	18	63	.1	26	11	442	3.13	15	<1	<2	3	11	.2	1.0	<.5	30	.08	.072	31	23	.41	201	.007	4	1.35	.008	.12	1	<1	2.0	<1	.02	4
01311	.3	33	20	66	.1	37	16	592	3.23	25	<1	<2	15	15	.2	.8	<.5	16	.16	.055	42	14	.30	88	.012	<1	.81	.006	.07	1	<1	2.4	1	<.01	2
01312	.3	34	21	64	<.1	39	17	563	3.22	13	1	<2	13	10	.2	.8	<.5	16	.10	.042	43	15	.36	165	.006	<1	.97	.005	.07	1	1	2.3	<1	<.01	3
01313	.3	33	20	70	<.1	42	17	595	3.15	6	1	<2	12	10	<.2	.8	<.5	7	.11	.049	38	9	.21	114	.002	1	.67	.003	.07	<1	<1	1.5	<1	.01	1
01314	.3	30	17	63	<.1	36	14	542	2.75	10	2	<2	16	9	.2	.6	<.5	8	.11	.044	42	8	.18	143	.002	3	.59	.004	.05	<1	<1	1.6	1	<.01	1
01315	.4	33	20	68	<.1	39	15	593	3.13	8	1	<2	13	9	<.2	<.5	<.5	12	.08	.046	47	11	.24	135	.005	2	.70	.004	.05	<1	<1	1.7	<1	<.01	1
01317	1.8	53	22	108	.2	61	23	964	4.38	66	1	<2	12	27	.5	1.1	2.0	22	.28	.084	39	19	.37	81	.016	<1	.94	.007	.09	3	1	3.3	1	.01	3
01318	1.2	47	22	98	.2	47	19	762	3.86	47	1	<2	13	54	.4	.7	1.2	24	.72	.074	42	20	.43	72	.017	<1	1.07	.008	.09	3	1	3.1	<1	<.01	3
01319	.6	49	21	85	.1	47	20	727	4.01	30	<1	<2	13	80	.3	<.5	<.5	29	1.35	.071	43	26	.59	72	.018	2	1.31	.014	.12	1	1	3.5	<1	<.01	3
01320	1.3	50	22	109	.2	57	22	1319	4.00	44	1	<2	12	59	.5	.7	.6	23	.88	.083	35	19	.42	83	.017	<1	.97	.009	.09	1	<1	3.1	<1	.01	2
01321	.5	50	20	80	.1	49	21	723	4.06	26	<1	<2	13	82	.3	<.5	<.5	29	1.41	.073	39	29	.67	79	.021	4	1.45	.011	.13	1	1	3.7	<1	<.01	3
01322	.5	22	14	68	.3	28	10	206	4.18	19	<1	<2	5	8	.3	1.1	.5	29	.11	.054	29	30	.51	75	.009	<1	1.49	.005	.07	1	<1	1.8	<1	.02	3
01323	.6	48	21	78	.2	45	19	726	3.70	32	1	<2	11	93	.3	<.5	<.5	24	2.18	.074	33	21	.47	63	.021	<1	.97	.010	.11	1	<1	3.3	<1	.02	1
01324	.9	47	21	86	.2	47	18	682	3.72	36	1	<2	10	57	.4	<.5	<.5	21	1.23	.081	34	18	.41	54	.021	1	.81	.008	.08	<1	1	3.0	<1	.02	1
01325	1.5	46	31	95	.3	50	18	809	3.87	49	2	<2	12	16	.4	1.2	.5	20	.16	.082	33	17	.28	84	.016	<1	.77	.005	.08	1	<1	3.0	1	<.01	1
RE 01325	1.4	45	30	93	.3	49	18	791	3.79	48	2	<2	12	14	.4	.8	.6	19	.15	.079	34	16	.28	82	.016	1	.76	.006	.07	1	<1	3.0	<1	<.01	1
01327	1.7	58	23	101	.2	64	19	782	4.68	113	2	<2	9	48	.7	1.0	1.1	25	.48	.112	27	18	.33	101	.027	1	.81	.013	.10	1	<1	3.1	<1	.02	2
01328	.6	48	16	73	.2	47	20	907	3.88	25	1	<2	9	81	.3	1.0	<.5	24	3.43	.055	23	26	.64	90	.020	2	1.14	.014	.17	1	1	3.9	<1	.02	1
01329	.4	11	11	34	.1	11	4	146	2.46	10	<1	<2	2	3	<.2	<.5	<.5	25	.05	.053	27	18	.19	58	.007	<1	.94	.005	.06	<1	<1	.9	<1	.01	3
01330	.5	13	12	50	.1	16	6	201	3.10	12	<1	<2	2	4	<.2	.6	<.5	28	.06	.065	24	23	.30	61	.010	<1	1.16	.005	.06	1	<1	1.2	<1	.01	3
01331	.8	34	16	75	.6	31	7	165	2.76	22	<1	<2	<1	29	.2	1.0	<.5	20	.09	.088	33	10	.06	55	.005	<1	.48	.005	.05	<1	<1	.6	<1	.02	2
01332	.7	17	14	37	.9	14	4	227	2.26	19	<1	<2	3	8	.2	.6	<.5	25	.04	.060	33	11	.09	53	.011	<1	.56	.004	.05	<1	<1	.9	<1	<.01	3
01333	.7	16	25	41	1.1	14	4	157	4.29	23	<1	<2	2	9	.3	.6	.7	33	.10	.098	24	22	.20	68	.012	<1	.88	.005	.04	1	<1	1.0	<1	.02	3
01334	.6	49	32	90	.1	48	18	611	3.63	23	1	<2	8	13	.4	1.0	<.5	28	.10	.056	37	22	.35	71	.023	1	1.13	.006	.07	1	<1	2.8	<1	.01	2
01336	2.9	80	23	178	.2	88	25	908	5.47	57	4	<2	10	23	.8	2.5	.9	16	.13	.136	32	13	.19	75	.011	<1	.57	.005	.06	1	<1	2.8	<1	.02	1
01337	1.0	53	28	100	.2	55	20	825	3.98	33	1	<2	11	21	3.6	.7	<.5	23	.37	.086	38	18	.38	74	.026	<1	.82	.007	.07	1	<1	3.2	<1	.01	<1
01338	.6	45	26	85	<.1	45	18	677	3.70	26	<1	<2	9	15	.3	<.5	<.5	29	.22	.077	38	23	.44	82	.026	1	1.08	.007	.09	<1	<1	3.5	<1	<.01	1
01339	2.4	11	8	30	.3	8	1	47	1.87	7	<1	<2	2	6	<.2	.5	<.5	28	.02	.069	20	16	.15	186	.012	<1	.60	.002	.05	<1	<1	1.1	<1	.01	3
01340	3.5	17	15	49	.2	15	2	94	3.92	13	1	<2	4	7	.2	1.0	<.5	41	.03	.108	20	26	.26	198	.024	3	.80	.003	.05	<1	<1	1.4	<1	.02	2
01341	3.6	17	13	41	.7	12	2	105	2.96	12	1	<2	3	7	<.2	.6	<.5	29	.02	.095	20	19	.20	223	.014	<1	.64	.002	.06	<1	<1	1.2	<1	.02	1
01342	4.6	19	16	51	.4	16	3	108	3.13	19	1	<2	4	12	<.2	1.1	<.5	50	.05	.219	20	19	.24	203	.025	1	.74	.004	.07	<1	<1	1.6	<1	.02	3
01343	4.3	20	26	58	1.0	18	4	280	4.12	18	1	<2	4	11	.2	1.4	<.5	55	.07	.198	22	25	.28	230	.026	2	.83	.003	.07	<1	<1	1.7	<1	.02	2
STANDARD C3	26.9	69	37	175	5.5	37	12	756	3.40	55	23	<2	21	30	25.0	15.9	22.5	82	.60	.095	19	183	.61	162	.090	20	1.81	.048	.18	16	2	4.5	1	.03	6
STANDARD G-2	1.6	2	3	45	<.1	8	4	532	2.03	<1	2	<2	5	80	<.2	<.5	<.5	44	.70	.101	8	83	.61	236	.131	<1	.95	.109	.52	3	<1	2.8	2	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01344	2.5	12	16	34	.3	10	2	119	2.69	13	<1	<2	4	9	<.2	.6	.7	38	.06	.293	21	21	.17	199	.019	2	.69	.003	.07	<1	<1	1.2	<1	.02	2
01345	2.5	19	7	38	<.1	12	2	62	1.46	8	<1	<2	3	13	<.2	.8	<.5	22	.11	.022	29	9	.06	240	.015	<1	.32	.002	.05	<1	<1	.8	<1	<.01	3
01346	2.0	40	10	26	3.0	22	3	455	.80	4	13	<2	2	197	.5	.9	<.5	5	2.20	.111	14	12	.23	730	.003	2	.57	.011	.07	<1	1	1.7	<1	.18	2
01347	1.7	21	9	40	.8	13	4	248	1.60	4	2	<2	3	35	<.2	<.5	<.5	19	.32	.033	25	13	.09	462	.009	<1	.55	.003	.07	<1	<1	1.9	1	.01	3
01348	2.2	38	18	48	1.7	26	10	888	2.27	6	3	<2	2	80	.3	<.5	<.5	22	.79	.092	16	17	.19	639	.006	<1	.96	.007	.09	<1	1	1.6	2	.06	2
01349	2.4	20	10	53	.1	19	5	100	2.12	9	1	<2	6	18	<.2	<.5	<.5	19	.12	.029	29	14	.23	420	.006	3	.66	.003	.06	<1	<1	1.3	<1	.01	1
01350	2.3	30	20	63	.1	21	7	315	3.66	9	1	<2	4	12	<.2	1.1	<.5	30	.08	.049	24	20	.19	207	.015	<1	.86	.004	.08	<1	<1	1.3	<1	.01	2
01351	.9	18	23	44	<.1	17	5	149	3.78	8	<1	<2	8	5	<.2	.8	<.5	20	.05	.065	38	14	.10	106	.002	<1	.86	.004	.08	<1	<1	1.2	<1	.02	<1
01352	.9	15	11	28	.3	10	4	117	1.94	7	<1	<2	1	28	<.2	<.5	<.5	22	.25	.035	25	13	.14	314	.010	3	.64	.004	.06	<1	<1	.9	<1	.01	3
01353	.8	25	20	57	<.1	27	13	477	3.08	12	1	<2	3	36	<.2	.6	<.5	29	.38	.055	24	26	.35	341	.011	<1	1.09	.005	.07	<1	<1	2.3	<1	.02	3
01354	1.0	22	3	24	.5	8	4	954	1.12	8	3	<2	1	251	.3	.7	<.5	4	3.66	.104	1	3	.25	252	.003	5	.14	.012	.03	<1	1	.5	<1	.34	1
01355	.4	19	24	76	.4	23	13	401	2.54	6	2	<2	4	27	<.2	<.5	<.5	25	.32	.072	25	26	.38	220	.012	<1	1.13	.005	.07	<1	<1	2.9	<1	.02	3
01356	.9	22	30	83	<.1	24	13	705	3.73	13	1	<2	5	9	<.2	.9	<.5	36	.09	.055	28	28	.35	260	.010	<1	1.47	.006	.09	1	<1	3.4	1	.01	3
01357	.6	20	24	57	.2	21	13	460	2.89	7	2	<2	4	15	<.2	.6	<.5	23	.15	.060	22	21	.31	217	.008	<1	1.09	.005	.07	1	<1	2.5	1	.03	2
01358	.7	15	26	61	<.1	20	10	369	3.01	9	1	<2	3	12	<.2	<.5	<.5	27	.16	.061	22	23	.29	149	.010	<1	1.04	.005	.07	1	<1	2.3	<1	.03	2
01359	1.4	57	16	115	<.1	50	14	304	3.08	11	3	<2	14	10	.4	1.2	<.5	9	.06	.039	42	11	.20	64	.006	<1	.60	.002	.03	<1	<1	1.8	<1	<.01	1
01360	1.3	57	16	118	.2	49	14	278	3.07	9	2	<2	14	15	.3	1.1	<.5	10	.12	.042	43	12	.26	78	.006	<1	.75	.002	.03	<1	<1	2.0	<1	<.01	1
01361	1.1	45	17	101	<.1	41	15	482	3.04	8	2	<2	12	14	.2	.9	<.5	11	.09	.044	41	12	.23	105	.007	<1	.74	.002	.04	<1	<1	2.0	1	<.01	1
01362	1.1	43	18	94	<.1	42	15	505	2.97	9	2	<2	12	11	.2	.7	<.5	10	.09	.042	40	10	.22	83	.008	<1	.65	.002	.03	<1	<1	1.9	<1	<.01	1
01363	.9	43	16	98	<.1	42	14	505	3.03	9	2	<2	13	9	.2	1.0	<.5	12	.07	.040	41	12	.23	83	.008	<1	.68	.002	.04	<1	1	2.0	<1	<.01	1
01364	.7	38	18	94	<.1	40	15	615	3.00	8	2	<2	14	9	.3	1.0	<.5	11	.08	.042	41	12	.24	88	.011	<1	.70	.003	.04	<1	<1	2.0	1	<.01	1
01369	.6	44	28	80	.6	45	16	566	3.35	27	3	<2	3	35	.3	1.2	<.5	26	.42	.075	31	22	.26	86	.013	<1	1.08	.008	.08	<1	1	3.1	<1	.02	2
01370	.4	32	26	64	.1	33	13	488	3.33	18	1	<2	4	16	<.2	1.0	<.5	32	.23	.050	33	26	.39	109	.011	<1	1.28	.006	.09	1	1	3.3	<1	.01	3
01371	.4	21	25	59	.1	25	11	326	3.37	18	1	<2	4	10	<.2	.5	<.5	33	.13	.042	28	26	.35	85	.010	<1	1.25	.005	.08	1	<1	2.1	<1	.01	4
RE 01371	.4	21	24	57	<.1	23	11	318	3.29	18	1	<2	3	10	<.2	.5	<.5	31	.13	.039	26	24	.34	80	.010	<1	1.21	.005	.07	1	<1	2.1	1	<.01	3
01465	.4	22	23	55	<.1	20	8	190	3.38	31	<1	<2	8	5	<.2	.7	.8	17	.06	.039	36	16	.25	60	.003	1	.95	.004	.07	1	<1	1.3	<1	<.01	2
01466	.3	41	26	61	<.1	34	18	1007	3.06	30	1	<2	8	19	.2	<.5	<.5	16	.27	.056	41	14	.27	50	.008	<1	.73	.004	.05	1	<1	2.0	<1	.01	2
01467	.5	36	25	76	.5	26	12	2229	3.10	18	3	<2	2	40	.3	<.5	<.5	24	.56	.123	29	20	.25	103	.007	<1	1.20	.007	.08	1	<1	2.0	<1	.04	3
01468	.4	18	14	39	<.1	11	6	323	2.01	17	<1	<2	2	14	<.2	<.5	.5	27	.16	.033	33	10	.09	65	.010	<1	.53	.004	.05	<1	<1	1.0	<1	<.01	4
01469	.4	33	26	67	.4	26	15	735	3.60	25	1	<2	3	36	.2	.6	.7	26	.56	.073	28	21	.25	83	.005	<1	1.18	.006	.09	1	1	2.1	<1	.02	3
01470	.6	49	31	71	.6	37	18	1456	3.79	25	3	<2	4	39	.3	<.5	.6	22	.61	.119	30	22	.29	88	.006	<1	1.30	.007	.10	2	<1	3.5	<1	.04	3
01471	.5	43	28	69	.5	35	15	1420	3.40	25	3	<2	2	50	.4	.8	.6	20	.74	.120	26	21	.25	91	.006	<1	1.23	.008	.10	1	<1	2.7	<1	.05	3
01473	.5	31	25	69	.1	34	16	453	3.80	25	1	<2	6	15	.2	.8	.5	21	.20	.046	29	23	.29	85	.005	<1	1.32	.006	.09	2	1	2.4	1	.01	3
01474	.6	41	30	81	.7	34	12	562	4.01	28	3	<2	4	24	.3	.5	<.5	30	.31	.068	31	24	.22	110	.006	<1	1.51	.007	.10	1	<1	3.0	<1	.03	4
STANDARD C3	26.3	71	35	173	5.5	38	12	766	3.24	55	23	<2	23	30	24.8	17.6	23.3	82	.60	.092	19	188	.62	161	.084	18	1.83	.046	.18	13	2	4.6	1	.03	6
STANDARD G-2	1.4	2	2	42	<.1	7	3	479	1.83	<1	2	<2	4	70	<.2	<.5	<.5	37	.61	.088	8	75	.55	207	.115	1	.82	.088	.46	2	1	2.4	<1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data__ FA ____

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01475	.8	74	33	109	1.3	65	23	1370	5.09	39	5	<2	7	33	.6	<.5	<.5	27	.46	.114	34	32	.35	120	.008	2	1.73	.008	.13	<1	<1	6.9	1	.04	4
01476	.5	40	26	68	.3	34	13	421	3.95	29	1	<2	5	17	.4	<.5	<.5	26	.21	.056	23	23	.21	118	.008	1	1.04	.005	.08	<1	<1	2.0	<1	.02	4
01477	.7	42	23	63	.4	27	10	356	3.65	25	1	<2	4	29	.3	<.5	.5	31	.34	.057	31	19	.20	78	.007	<1	1.09	.005	.08	1	<1	2.2	<1	.02	4
01478	.7	54	26	87	.8	51	19	1058	4.37	35	3	<2	6	41	.3	<.5	<.5	25	.57	.108	39	27	.40	98	.006	1	1.57	.007	.12	1	1	4.7	<1	.04	4
01479	.6	38	26	81	.5	41	19	769	4.20	36	2	<2	6	22	.2	<.5	<.5	26	.29	.073	29	24	.37	87	.005	<1	1.39	.006	.10	1	1	3.2	2	.02	3
01480	.5	22	16	59	.3	25	10	415	3.22	25	1	<2	4	14	<.2	<.5	<.5	27	.15	.049	29	19	.33	67	.007	<1	1.17	.004	.07	<1	<1	1.8	1	<.01	4
01481	.6	31	24	78	.1	35	15	522	4.05	43	1	<2	7	13	.2	<.5	<.5	31	.14	.062	33	26	.42	114	.007	<1	1.46	.005	.09	<1	1	2.7	<1	<.01	4
01482	.4	20	17	56	.1	23	8	295	3.68	23	<1	<2	4	10	.2	.6	<.5	30	.11	.051	24	24	.38	73	.008	2	1.23	.005	.05	<1	<1	1.5	<1	.01	4
01483	.7	41	28	76	.7	47	19	1137	4.23	43	2	<2	6	23	.3	<.5	.6	29	.34	.098	32	28	.44	85	.008	<1	1.65	.007	.10	<1	1	3.8	1	.02	4
01484	.5	36	21	74	.2	42	17	743	4.07	31	1	<2	7	16	.2	<.5	<.5	30	.22	.068	35	26	.50	74	.010	<1	1.46	.005	.08	1	<1	3.3	1	.01	3
01485	.4	36	18	68	.1	42	17	488	3.72	28	1	<2	9	15	.2	.5	<.5	29	.21	.075	38	25	.49	54	.011	<1	1.30	.004	.07	1	<1	3.1	<1	<.01	4
01486	.3	9	10	38	<.1	12	5	194	2.18	14	<1	<2	2	6	<.2	<.5	<.5	24	.06	.045	28	16	.25	54	.008	<1	.94	.004	.06	<1	<1	.9	1	.01	6
01487	.6	9	4	21	.1	7	2	93	1.21	14	<1	<2	3	5	<.2	<.5	<.5	18	.05	.021	37	6	.02	28	.004	<1	.37	.006	.03	<1	<1	.5	1	<.01	5
01490	.3	6	10	17	.1	4	1	53	.70	6	<1	<2	2	11	<.2	<.5	<.5	14	.16	.022	42	6	.06	87	.008	<1	.42	.004	.05	<1	<1	.4	<1	<.01	5
01491	.5	9	6	27	<.1	9	3	85	1.23	15	<1	<2	5	4	<.2	<.5	<.5	20	.04	.029	36	5	.02	29	.005	<1	.50	.004	.03	<1	<1	.6	1	<.01	5
01493	.2	3	5	9	<.1	2	1	44	.33	1	<1	<2	4	5	<.2	<.5	<.5	8	.04	.022	40	5	.03	48	.003	1	.72	.005	.03	<1	<1	.4	1	<.01	6
01494	1.1	28	33	66	.1	27	21	4301	3.39	14	2	<2	3	24	.3	<.5	.5	28	.33	.109	26	22	.21	117	.006	<1	1.37	.005	.05	1	<1	1.3	5	.04	2
01496	.7	11	4	24	.1	9	3	81	1.35	35	<1	<2	3	4	<.2	<.5	<.5	22	.02	.031	29	6	.02	16	.004	<1	.40	.005	.02	1	<1	.5	<1	<.01	4
01498	.4	9	14	33	<.1	10	3	83	2.58	22	<1	<2	5	4	<.2	<.5	<.5	22	.03	.047	31	14	.20	41	.004	<1	.89	.003	.04	1	<1	.9	<1	.01	4
01499	.5	17	14	59	<.1	18	7	142	4.11	20	<1	<2	7	5	<.2	1.1	<.5	24	.07	.048	31	22	.35	39	.004	<1	1.25	.003	.05	1	<1	1.3	<1	.01	3
01500	.3	20	17	59	<.1	23	9	191	3.87	25	<1	<2	7	5	<.2	<.5	<.5	24	.05	.043	32	22	.40	53	.004	<1	1.18	.003	.05	1	<1	1.4	<1	.01	2
RE 01500	.3	20	17	59	<.1	23	8	191	3.79	25	<1	<2	7	6	<.2	<.5	<.5	24	.05	.043	33	22	.40	53	.004	<1	1.20	.004	.05	<1	<1	1.5	<1	.01	2
01501	.4	31	24	71	.1	30	11	334	3.62	28	1	<2	5	15	<.2	<.5	<.5	30	.17	.067	31	22	.33	118	.005	<1	1.34	.006	.11	1	<1	1.8	<1	.01	3
01502	.3	24	22	75	<.1	30	13	584	3.68	26	1	<2	5	14	.3	<.5	.5	29	.16	.062	33	24	.38	88	.007	<1	1.38	.005	.09	<1	<1	2.3	1	.01	4
01503	.3	20	17	63	.1	25	10	384	3.36	23	1	<2	5	7	<.2	.6	<.5	24	.07	.044	32	22	.42	49	.005	<1	1.29	.003	.06	<1	<1	1.5	<1	<.01	3
01504	.4	16	19	60	<.1	18	7	153	4.00	24	<1	<2	7	5	.2	1.0	<.5	24	.05	.033	30	21	.35	45	.005	<1	1.15	.004	.05	1	<1	1.2	<1	.01	2
01505	.4	53	29	98	.8	47	16	997	4.16	31	8	<2	8	24	.3	.9	<.5	22	.24	.108	45	26	.32	110	.006	<1	1.72	.008	.12	1	1	5.1	<1	.04	2
01506	.5	14	15	47	.4	14	5	310	2.53	22	1	<2	4	16	<.2	<.5	<.5	20	.22	.055	29	14	.17	63	.006	<1	.88	.004	.07	<1	<1	1.1	<1	<.01	3
01507	.5	22	22	64	<.1	22	8	226	4.11	32	1	<2	9	6	<.2	.7	1.0	17	.07	.057	29	19	.27	50	.004	<1	1.06	.005	.06	1	<1	1.2	<1	.01	<1
01508	.5	17	14	54	<.1	18	7	198	3.34	21	<1	<2	6	9	<.2	<.5	<.5	24	.14	.040	27	18	.24	61	.005	<1	1.14	.004	.05	1	<1	1.3	<1	<.01	2
01509	.5	14	9	41	.2	14	6	289	2.52	17	<1	<2	3	5	<.2	<.5	<.5	24	.05	.040	27	16	.21	78	.005	<1	.95	.004	.07	<1	<1	.9	<1	<.01	4
01510	.5	35	17	70	.1	42	16	461	4.19	25	1	<2	7	6	.2	<.5	<.5	28	.10	.089	28	29	.45	65	.010	<1	1.37	.005	.08	1	<1	2.4	<1	.01	2
01511	.5	37	17	83	<.1	50	16	398	4.21	28	1	<2	6	6	.2	.9	<.5	28	.10	.055	28	32	.52	82	.011	<1	1.54	.005	.07	<1	<1	2.3	<1	<.01	2
01512	.7	20	17	66	<.1	27	10	217	5.07	27	<1	<2	7	4	<.2	1.4	<.5	30	.04	.068	23	31	.36	56	.011	<1	1.41	.004	.05	<1	<1	1.7	<1	.01	3
STANDARD C3	27.0	69	37	178	5.7	38	12	798	3.40	58	23	<2	22	29	24.2	16.7	22.8	84	.60	.096	19	184	.63	158	.091	18	1.85	.042	.18	16	2	4.5	<1	.03	5
STANDARD G-2	1.6	4	2	46	<.1	8	4	542	2.02	1	3	<2	5	74	<.2	<.5	<.5	44	.66	.104	8	82	.62	234	.133	<1	.94	.080	.51	2	1	2.7	<1	<.01	6

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01513	.7	24	16	56	1.1	23	6	203	2.90	20	<1	<2	1	8	<.2	.7	<.5	25	.07	.120	25	13	.13	49	.006	<1	.62	.005	.04	1	<1	.8	<1	.02	4
01514	.5	13	13	34	.4	12	4	143	2.18	18	<1	<2	2	5	<.2	.5	<.5	31	.04	.076	31	9	.08	33	.009	3	.60	.005	.04	1	<1	.9	<1	<.01	5
01515	.7	46	41	108	.9	39	13	529	4.83	25	1	<2	4	8	.2	1.2	.5	29	.04	.130	26	22	.26	59	.007	<1	1.06	.005	.07	<1	<1	1.5	<1	.02	5
01516	.4	24	25	70	.1	25	13	568	4.02	22	1	<2	2	11	<.2	<.5	<.5	28	.16	.060	24	23	.29	61	.010	1	1.07	.006	.06	<1	<1	1.4	<1	.01	3
01517	.5	25	23	85	.1	28	16	550	4.12	22	1	<2	4	15	<.2	<.5	<.5	28	.17	.061	28	23	.34	69	.011	<1	1.19	.005	.07	1	1	1.6	<1	.01	4
01518	.5	32	34	73	<.1	30	12	325	5.35	25	<1	<2	3	9	<.2	.9	<.5	24	.11	.069	24	22	.32	57	.010	1	1.12	.004	.05	1	<1	1.6	<1	.02	3
01519	.5	36	34	94	.6	33	17	1143	4.24	18	4	<2	3	39	<.2	<.5	<.5	23	.69	.133	24	23	.35	85	.007	<1	1.46	.006	.08	<1	1	3.6	1	.04	3
01520	.6	39	22	80	1.1	31	12	1010	2.55	12	8	<2	1	116	.3	<.5	<.5	13	2.26	.134	20	14	.27	71	.006	3	.96	.008	.05	<1	1	2.0	1	.13	1
01521	.3	28	28	78	.3	29	14	837	3.98	19	3	<2	4	34	.3	<.5	<.5	25	.61	.065	23	24	.34	77	.008	<1	1.24	.006	.07	1	1	2.7	<1	.02	3
01522	.6	63	37	98	2.2	50	19	1589	3.97	20	11	<2	4	76	.3	<.5	<.5	20	1.47	.152	43	26	.33	124	.007	1	1.63	.009	.11	1	<1	5.2	<1	.10	2
01524	.4	27	27	59	.2	28	14	408	3.66	25	1	<2	4	22	.2	<.5	<.5	24	.34	.057	28	19	.32	75	.006	<1	1.17	.007	.09	1	<1	2.4	<1	.02	3
01525	.3	28	33	65	.1	26	12	396	3.91	34	1	<2	6	7	.2	.7	<.5	17	.09	.041	30	15	.29	67	.003	<1	1.00	.005	.07	1	<1	1.8	<1	.01	1
RE 01525	.2	29	33	64	.1	27	13	405	4.06	34	<1	<2	5	8	<.2	.8	<.5	19	.09	.041	32	15	.30	67	.004	<1	1.03	.005	.07	1	<1	1.8	<1	.01	2
01526	.7	46	38	105	.3	42	18	721	5.31	40	1	<2	7	12	.3	.8	<.5	30	.16	.071	33	26	.31	102	.006	<1	1.54	.006	.12	1	1	3.2	<1	.02	4
01527	.7	38	37	97	.2	29	13	695	4.91	34	1	<2	3	10	.4	1.5	<.5	30	.12	.071	29	21	.22	142	.008	<1	1.17	.005	.09	1	1	1.8	1	.02	4
01528	.2	38	29	76	.6	32	12	692	3.46	22	4	<2	7	19	<.2	<.5	<.5	19	.24	.094	29	18	.29	78	.004	1	1.26	.006	.08	1	1	3.6	<1	.04	2
01530	.3	31	28	62	<.1	21	9	295	3.94	25	2	<2	7	8	<.2	<.5	<.5	24	.08	.049	29	20	.27	56	.004	<1	1.24	.005	.07	1	<1	1.7	<1	.01	2
01531	.3	31	28	70	<.1	24	11	329	4.09	26	2	<2	7	9	<.2	.7	<.5	22	.07	.054	29	23	.31	62	.004	<1	1.31	.005	.07	<1	<1	1.7	<1	.01	3
01533	.3	39	23	57	.3	23	11	243	3.20	19	3	<2	7	14	.3	<.5	<.5	27	.16	.035	38	18	.20	58	.004	<1	1.18	.005	.06	<1	<1	2.6	<1	.01	3
01534	.4	47	32	96	.9	41	18	636	4.08	23	4	<2	8	30	.6	<.5	<.5	25	.53	.090	45	24	.43	97	.004	<1	1.64	.006	.09	1	1	4.8	<1	.03	3
01535	.7	72	49	103	.6	46	23	720	5.09	34	3	<2	8	26	.6	.7	<.5	32	.43	.068	38	27	.39	105	.006	<1	1.77	.007	.12	1	1	4.1	<1	.02	4
01536	<.2	33	34	73	.5	36	15	259	3.67	39	2	<2	7	22	.3	<.5	<.5	27	.29	.066	42	19	.45	82	.005	<1	1.41	.007	.09	1	<1	3.2	<1	.01	3
01537	.4	64	60	103	<.1	66	32	1033	5.10	77	3	<2	13	10	.4	1.2	<.5	28	.10	.058	57	27	.48	131	.005	<1	1.88	.007	.14	1	1	6.4	3	.02	3
01538	.3	18	16	64	.1	20	8	155	4.20	24	<1	<2	10	3	<.2	.7	<.5	25	.03	.039	35	24	.41	47	.004	<1	1.42	.004	.06	2	<1	1.6	<1	.01	3
01539	.5	20	23	58	.1	20	8	186	4.84	20	<1	<2	7	4	<.2	<.5	<.5	30	.03	.047	32	27	.42	43	.005	1	1.42	.003	.05	1	<1	1.8	<1	.01	3
01540	.3	11	17	38	<.1	12	5	125	4.05	29	<1	<2	8	4	<.2	.6	<.5	36	.02	.064	33	18	.25	47	.008	<1	.98	.004	.05	1	<1	1.1	<1	<.01	3
01541	.6	10	9	30	.1	9	3	174	1.92	46	<1	<2	5	3	<.2	<.5	<.5	16	.03	.037	35	5	.03	21	.002	<1	.58	.005	.03	1	<1	.8	<1	<.01	2
01542	.5	5	3	14	<.1	5	2	62	.88	22	<1	<2	3	3	<.2	<.5	<.5	14	.04	.033	36	5	.02	16	.002	1	.40	.004	.02	<1	<1	.6	2	<.01	5
01543	.4	7	4	13	<.1	6	2	42	.88	23	<1	<2	4	3	<.2	<.5	<.5	15	.01	.025	33	2	.01	9	.003	1	.33	.002	.02	<1	<1	.4	1	<.01	5
01544	.8	16	12	55	.1	23	8	430	3.60	23	<1	<2	3	24	<.2	<.5	<.5	43	.29	.056	24	52	.40	64	.005	<1	1.23	.006	.04	<1	<1	2.3	<1	.02	5
01545	.6	14	12	43	.2	13	4	182	2.35	20	<1	<2	2	6	<.2	<.5	<.5	30	.06	.059	33	11	.09	36	.006	<1	.67	.006	.05	<1	<1	.7	<1	.01	4
01546	.8	26	24	76	<.1	27	10	435	5.60	33	1	<2	6	4	<.2	1.2	.6	27	.02	.089	30	26	.28	82	.005	<1	1.11	.004	.08	1	<1	1.5	1	.01	4
01547	.4	4	5	11	<.1	3	1	34	.57	14	<1	<2	4	3	<.2	<.5	<.5	16	.02	.016	38	4	.02	14	.004	1	.36	.003	.03	1	<1	.5	1	<.01	5
01548	.6	120	66	114	1.8	91	22	3352	4.33	31	11	<2	9	41	.8	1.1	<.5	23	.62	.280	32	26	.30	111	.012	2	2.46	.009	.09	<1	<1	3.6	<1	.11	<1
STANDARD C3	27.8	71	36	179	5.8	39	13	836	3.45	55	24	2	23	30	24.8	17.8	23.6	86	.63	.102	20	179	.67	167	.090	20	1.84	.045	.18	15	2	4.6	<1	.03	6
STANDARD G-2	1.6	4	3	48	<.1	8	4	570	2.14	<1	2	<2	4	77	<.2	<.5	<.5	47	.71	.109	8	81	.65	252	.136	7	.96	.100	.54	2	1	2.6	1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01549	.8	18	20	92	<.1	26	8	191	5.96	20	1	<2	11	10	.2	.5	<.5	24	.13	.049	28	32	.61	71	.003	<1	2.00	.003	.04	<1	1	1.4	<1	.02	6
01550	.6	16	23	54	<.1	14	5	313	2.93	38	1	<2	9	13	<.2	<.5	<.5	31	.15	.062	33	15	.15	74	.007	2	.98	.005	.05	1	<1	1.2	<1	.02	3
01551	.8	25	12	48	<.1	10	8	203	3.82	16	1	<2	3	5	<.2	<.5	<.5	79	.04	.056	23	10	.18	35	.005	1	1.16	.004	.03	<1	<1	1.8	<1	.02	5
01552	.9	22	24	56	.1	19	6	188	3.34	49	1	<2	3	5	.2	<.5	.6	35	.03	.044	29	13	.05	42	.010	<1	.66	.003	.03	1	<1	.8	<1	.01	2
01553	.6	50	24	52	.4	34	11	547	2.97	24	3	<2	2	25	.3	<.5	<.5	24	.35	.085	23	16	.16	78	.008	4	.88	.006	.05	<1	<1	1.1	<1	.03	2
01554	.6	40	26	74	.2	37	15	1316	3.42	26	4	<2	3	18	.3	.8	<.5	18	.27	.111	23	18	.28	52	.008	<1	1.17	.005	.06	<1	<1	1.9	<1	.04	1
01555	.6	11	5	26	.1	10	3	82	1.43	13	<1	<2	4	5	<.2	<.5	<.5	19	.06	.029	29	6	.02	36	.004	3	.45	.003	.03	<1	<1	.5	<1	<.01	4
01556	.7	12	11	35	.3	14	5	536	2.31	15	1	<2	3	17	<.2	<.5	<.5	25	.23	.050	24	21	.22	77	.006	1	1.10	.005	.05	<1	<1	1.2	1	.01	4
01557	.8	13	12	40	.4	15	6	1731	2.40	14	1	<2	3	17	<.2	<.5	<.5	25	.22	.060	25	21	.22	102	.005	1	1.16	.005	.05	<1	<1	1.2	<1	.02	4
01558	.8	28	13	43	<.1	21	8	181	2.71	44	1	<2	8	4	<.2	.6	.5	26	.02	.058	42	8	.02	16	.005	<1	.47	.003	.03	1	<1	.9	1	<.01	2
01559	.5	16	10	40	<.1	14	5	137	2.27	36	<1	<2	4	5	<.2	.5	<.5	35	.04	.059	33	10	.08	30	.012	1	.65	.003	.04	<1	<1	.9	<1	<.01	4
01560	.5	10	6	27	<.1	9	3	86	1.41	23	<1	<2	4	4	<.2	<.5	<.5	21	.03	.041	35	6	.04	28	.005	<1	.59	.003	.03	<1	<1	.5	<1	<.01	4
01561	.6	12	15	48	.3	12	5	146	3.54	14	1	<2	5	5	<.2	<.5	<.5	29	.06	.050	17	23	.31	56	.009	2	1.32	.005	.04	1	<1	1.2	<1	.02	3
01562	.6	25	32	62	.2	27	11	198	5.09	26	1	<2	7	6	.2	1.0	<.5	23	.05	.054	18	23	.37	64	.005	2	1.49	.004	.06	<1	1	1.6	1	.02	2
01563	.3	12	14	39	<.1	12	5	309	2.52	18	<1	<2	9	4	<.2	<.5	<.5	22	.02	.023	30	14	.22	57	.006	<1	1.02	.004	.06	<1	<1	1.3	<1	<.01	4
01564	.4	16	18	47	<.1	16	7	406	2.96	20	1	<2	7	6	<.2	<.5	<.5	25	.03	.033	32	17	.23	84	.006	<1	1.18	.005	.07	1	<1	1.8	<1	<.01	4
01565	.4	6	6	16	<.1	5	2	36	.92	12	<1	<2	4	10	<.2	<.5	<.5	16	.11	.029	26	7	.10	59	.003	1	.57	.003	.04	<1	<1	.5	<1	<.01	5
RE 01565	.4	6	6	17	<.1	5	2	37	.94	12	<1	<2	4	10	<.2	<.5	<.5	16	.11	.029	27	8	.10	59	.003	1	.58	.004	.04	1	<1	.6	<1	<.01	5
01566	.7	28	29	63	.2	19	7	191	4.31	28	1	<2	3	11	.3	.8	<.5	27	.13	.055	25	21	.29	97	.006	2	1.17	.005	.07	1	<1	1.3	<1	.02	4
01567	.6	32	33	56	.4	26	13	427	3.69	35	1	<2	4	19	.4	<.5	<.5	23	.23	.070	31	18	.27	67	.006	2	1.16	.005	.08	1	<1	2.2	<1	.02	3
01568	.5	38	32	80	.2	44	16	677	3.88	35	2	<2	8	27	.3	<.5	<.5	21	.36	.080	33	21	.42	100	.004	1	1.48	.006	.10	1	<1	3.6	<1	.02	2
01569	.5	30	23	72	.3	31	12	552	3.23	29	2	<2	6	24	.3	<.5	<.5	17	.27	.075	29	18	.29	70	.005	<1	1.04	.004	.07	1	<1	2.6	2	.02	2
01570	.6	29	26	64	.4	25	10	382	3.32	28	2	<2	5	14	.2	<.5	<.5	19	.17	.075	27	18	.30	71	.005	<1	1.15	.004	.08	1	<1	2.2	1	.02	3
01572	.5	26	14	39	.3	14	5	191	2.12	27	1	<2	3	36	.2	<.5	<.5	17	.55	.040	23	9	.07	45	.006	<1	.60	.004	.06	1	<1	1.1	<1	.02	2
01573	.8	67	29	74	2.0	42	13	1178	3.37	32	6	<2	3	77	.5	<.5	<.5	20	1.26	.143	58	20	.24	95	.007	<1	1.38	.007	.09	1	<1	3.1	1	.08	2
01574	.7	52	39	81	1.2	35	17	1072	3.39	27	5	<2	3	84	.4	<.5	<.5	18	1.36	.108	23	20	.26	76	.005	<1	1.10	.006	.07	1	<1	2.9	<1	.07	2
01575	.8	40	36	111	.4	28	16	1700	4.08	30	4	<2	5	16	.4	.7	.6	21	.12	.067	27	20	.22	82	.007	<1	1.19	.004	.06	1	<1	3.0	1	.02	3
01576	.7	49	40	90	.7	40	16	1224	3.83	34	6	<2	3	53	.6	<.5	<.5	18	.86	.115	34	21	.26	87	.006	1	1.28	.006	.08	1	<1	3.6	<1	.06	2
01577	.9	68	49	96	.2	47	23	770	4.61	38	5	<2	10	9	.3	1.3	.5	23	.10	.093	54	24	.30	81	.005	1	1.76	.005	.10	1	<1	6.3	<1	.03	3
01578	.7	44	43	87	.5	35	15	602	4.07	34	3	<2	6	11	.2	.5	<.5	20	.13	.112	35	21	.27	70	.006	1	1.37	.005	.10	1	<1	3.8	1	.03	3
01579	.7	21	26	63	.7	24	9	224	3.82	27	1	<2	5	7	.2	<.5	<.5	29	.08	.067	23	22	.27	99	.013	1	.99	.004	.06	1	<1	1.7	<1	.01	4
01580	.6	14	21	48	.4	18	6	170	3.38	15	<1	<2	3	5	.2	<.5	<.5	31	.08	.069	22	26	.36	80	.011	<1	1.16	.004	.06	<1	<1	1.2	1	.01	5
01581	.9	19	26	49	.4	18	6	170	4.70	29	<1	<2	3	9	.2	<.5	<.5	25	.12	.070	20	20	.23	64	.009	<1	.94	.004	.05	1	<1	1.1	<1	.02	3
01582	.6	9	16	25	.1	9	3	87	2.24	21	<1	<2	1	8	.2	<.5	.5	24	.13	.078	21	10	.11	50	.007	2	.71	.004	.05	1	<1	.6	<1	.01	4
STANDARD C3	27.0	67	36	172	5.4	38	12	791	3.36	57	24	<2	22	29	24.6	16.6	22.5	80	.60	.097	19	179	.64	161	.088	25	1.83	.043	.17	15	2	4.4	1	.03	6
STANDARD G-2	1.6	4	3	46	<.1	8	4	541	2.03	<1	2	<2	4	74	<.2	<.5	<.5	42	.66	.105	7	79	.63	237	.128	3	.95	.089	.52	2	1	2.5	<1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data A

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01583	.9	53	85	65	1.4	38	15	3563	3.34	15	4	<2	5	48	.6	<.5	.5	30	.81	.121	37	24	.19	131	.009	3	1.57	.008	.10	1	<1	3.7	<1	.05	3
01584	.7	18	22	54	.1	18	7	239	4.04	20	1	<2	4	12	<.2	<.5	<.5	33	.15	.072	26	18	.20	99	.016	3	.85	.004	.06	1	<1	1.2	<1	.01	4
01585	1.1	54	26	71	.1	49	11	406	3.62	84	1	<2	2	25	.3	7.9	.6	33	.07	.104	33	13	.07	62	.010	5	.63	.005	.05	1	<1	1.5	<1	.02	3
01586	.5	29	33	61	4.5	24	8	158	3.65	24	1	<2	5	11	.2	.8	<.5	26	.07	.125	26	14	.16	61	.010	1	.65	.004	.05	1	<1	1.2	<1	.02	3
01587	.8	39	26	87	.5	35	12	329	3.85	24	1	<2	3	28	.3	1.4	1.1	31	.25	.060	32	16	.10	84	.016	1	.63	.005	.05	<1	<1	1.6	<1	.02	3
01588	.2	24	22	58	.1	29	10	204	3.71	11	1	<2	5	7	<.2	<.5	<.5	30	.09	.059	24	31	.47	70	.013	4	1.27	.006	.07	<1	1	1.9	<1	.02	4
01589	.6	44	21	70	.5	28	14	444	4.97	14	1	<2	3	9	<.2	<.5	<.5	48	.11	.077	20	24	.58	129	.009	2	1.46	.005	.07	<1	1	2.4	<1	.02	6
01590	.4	11	14	31	.1	11	4	122	2.83	8	1	<2	4	5	<.2	<.5	<.5	28	.05	.057	18	15	.23	67	.009	2	.98	.004	.06	<1	<1	1.2	<1	.02	5
01591	.6	18	18	40	.1	14	5	187	3.87	18	1	<2	3	12	<.2	<.5	<.5	33	.15	.044	29	15	.15	68	.015	3	.82	.004	.05	1	<1	1.0	<1	.01	3
01592	.4	29	21	43	.4	15	6	220	3.20	13	3	<2	2	6	.2	<.5	<.5	23	.05	.065	21	17	.21	46	.008	<1	.99	.004	.05	1	<1	1.0	<1	.02	3
01593	.2	10	13	26	.2	8	4	290	2.17	14	<1	<2	2	4	<.2	<.5	<.5	20	.03	.073	25	12	.17	44	.008	<1	.72	.004	.05	<1	<1	.7	<1	<.01	5
01594	.4	17	16	44	.1	14	6	217	4.04	17	1	<2	4	5	<.2	<.5	<.5	24	.05	.101	22	17	.27	51	.006	<1	1.06	.004	.06	1	<1	1.0	<1	.02	2
01595	.4	6	11	19	.2	5	2	148	2.03	10	<1	<2	2	3	<.2	<.5	<.5	24	.03	.064	24	9	.10	44	.006	<1	.60	.003	.05	1	<1	.7	<1	<.01	4
RE 01595	.3	6	11	20	.2	5	2	151	2.09	11	<1	<2	2	4	<.2	<.5	<.5	24	.03	.064	24	9	.10	43	.006	<1	.61	.004	.05	1	<1	.7	<1	<.01	4
01596	.3	7	12	21	.3	6	2	124	1.92	6	<1	<2	4	4	<.2	<.5	<.5	22	.02	.045	22	10	.13	55	.005	3	.84	.005	.06	1	<1	.9	<1	<.01	4
01597	.2	18	16	46	.1	19	7	253	3.90	24	1	<2	5	6	.2	<.5	<.5	21	.05	.084	25	19	.27	59	.005	<1	.97	.004	.06	1	<1	1.1	<1	.02	3
01598	.7	21	22	48	.3	20	7	224	5.36	27	1	<2	8	3	<.2	1.2	<.5	22	.03	.058	26	23	.28	43	.006	<1	1.16	.004	.07	1	<1	1.5	1	.01	3
01599	.4	5	9	14	.1	5	1	104	1.45	18	<1	<2	6	4	<.2	<.5	<.5	21	.03	.036	39	8	.08	42	.005	2	.67	.004	.06	1	<1	.7	<1	<.01	6
01600	.3	8	21	27	.3	8	2	87	3.15	26	<1	<2	9	5	<.2	<.5	<.5	18	.04	.061	33	13	.14	44	.004	<1	.77	.004	.07	1	<1	.8	<1	<.01	3
01622	4.5	40	43	85	.6	25	3	74	4.20	28	2	<2	3	57	.3	4.2	<.5	81	.02	.167	21	17	.08	135	.017	2	.60	.004	.06	<1	<1	1.5	<1	.06	4
01623	.7	4	12	9	.6	3	<1	25	1.93	4	<1	<2	2	4	<.2	<.5	<.5	17	.02	.047	18	7	.03	22	.005	3	.45	.003	.02	<1	<1	.4	<1	.02	2
01624	2.3	18	20	46	.9	14	3	114	5.30	3	1	<2	8	6	<.2	1.2	<.5	22	.02	.081	24	25	.17	48	.011	<1	1.00	.003	.04	<1	1	1.1	<1	.02	2
01625	.8	6	8	13	.1	5	1	47	1.86	2	<1	<2	4	4	<.2	<.5	<.5	17	.02	.052	23	10	.06	49	.008	<1	.59	.002	.03	<1	<1	.7	<1	<.01	4
01626	3.2	27	95	125	.2	24	5	510	6.65	22	1	<2	8	5	.2	1.6	<.5	23	.01	.077	25	25	.19	141	.005	1	1.06	.004	.08	<1	<1	2.3	2	.02	3
01627	3.0	27	122	153	.2	27	6	671	6.89	23	1	<2	8	5	.2	1.1	.5	23	.02	.079	25	24	.18	136	.006	<1	1.02	.003	.07	<1	1	2.7	2	.02	3
01628	1.8	16	10	42	<.1	13	3	90	2.26	9	<1	<2	3	15	<.2	<.5	<.5	26	.17	.046	21	13	.15	142	.011	1	.52	.002	.05	<1	<1	.9	<1	<.01	2
01629	1.4	17	16	58	.2	20	6	258	3.72	7	1	<2	7	9	<.2	<.5	.5	30	.10	.036	23	25	.28	155	.020	1	.92	.004	.06	<1	<1	1.6	<1	.01	2
01630	1.4	21	19	67	.1	21	6	144	3.71	8	1	<2	9	6	<.2	.9	<.5	25	.05	.067	29	16	.18	105	.008	1	.74	.003	.06	<1	<1	1.2	<1	.01	3
01631	.7	27	20	62	.2	21	7	229	3.30	7	2	<2	3	10	.2	<.5	<.5	19	.13	.054	21	16	.13	136	.005	<1	.91	.004	.07	<1	<1	1.3	<1	.01	1
01632	1.2	31	11	67	.1	71	25	421	6.40	9	<1	<2	2	6	.2	1.0	<.5	26	.03	.076	14	24	.11	165	.012	<1	.73	.003	.04	<1	<1	2.3	1	.02	3
01633	1.6	19	11	44	<.1	14	4	95	2.72	18	<1	<2	4	7	<.2	<.5	<.5	32	.06	.042	30	8	.02	82	.012	<1	.37	.002	.04	<1	<1	.9	<1	<.01	2
01635	1.3	11	26	31	.2	13	3	121	4.27	12	1	<2	3	6	<.2	.6	<.5	32	.06	.145	19	22	.14	75	.009	2	.70	.003	.05	<1	<1	.7	<1	.02	1
01636	.9	10	17	27	.2	9	2	79	3.10	12	1	<2	5	6	<.2	.5	<.5	25	.04	.143	23	15	.12	57	.009	<1	.66	.002	.05	<1	<1	1.0	<1	.01	2
01637	1.0	15	10	41	.1	17	5	156	2.95	9	<1	<2	2	13	<.2	<.5	<.5	29	.17	.055	20	23	.24	121	.008	1	.77	.003	.05	<1	<1	1.1	<1	.01	3
STANDARD C3	29.0	71	38	179	5.8	39	12	833	3.54	57	25	<2	24	30	24.8	19.4	24.4	87	.63	.100	20	186	.66	167	.091	23	1.84	.047	.19	15	2	4.8	2	.03	6
STANDARD G-2	1.6	4	3	44	<.1	8	4	553	2.07	<1	2	<2	6	86	<.2	<.5	<.5	44	.70	.105	8	86	.63	250	.135	<1	1.02	.088	.57	2	1	2.7	1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ~ FA ____

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01638	2.3	62	13	138	.4	87	28	517	4.48	12		<2	7	18	1.0	5.2	<.5	27	.26	.144	25	32	.30	87	.008	3	1.01	.005	.05	1	<1	3.3	1	.01	2
01639	.8	20	11	56	.1	33	9	252	3.00	8		<2	1	12	.2	<.5	<.5	35	.16	.079	23	39	.31	90	.008	<1	.90	.005	.05	<1	<1	1.8	<1	.01	4
01641	3.8	34	16	167	<.1	50	13	328	3.25	72		<2	1	10	.5	5.4	.8	32	.06	.068	23	10	.05	57	.005	2	.41	.005	.03	1	<1	1.4	1	<.01	2
01644	2.0	67	38	118	.6	70	20	543	4.39	86		<2	6	21	.7	1.1	3.2	29	.21	.116	27	26	.38	71	.026	<1	1.09	.007	.06	1	1	3.8	<1	<.01	3
01670	4.0	27	9	55	.2	19	3	112	2.96	10		<2	3	7	<.2	.9	<.5	44	.01	.085	26	13	.05	102	.011	3	.50	.004	.04	<1	<1	.8	<1	.01	4
01671	2.1	24	7	51	<.1	18	4	104	1.80	8		<2	5	7	<.2	<.5	<.5	41	.01	.048	28	11	.06	73	.017	<1	.49	.003	.03	<1	<1	1.0	<1	<.01	7
01672	2.8	13	15	38	.7	11	2	75	4.05	7		<2	5	6	<.2	1.0	<.5	70	.02	.103	22	25	.14	132	.020	<1	.89	.003	.05	<1	<1	1.2	<1	.01	4
01673	3.2	24	15	61	<.1	20	4	99	4.10	8		<2	5	9	<.2	1.0	<.5	40	.02	.045	20	25	.24	145	.015	1	.99	.003	.05	<1	<1	1.5	<1	.02	3
01674	4.3	21	17	88	.1	26	5	130	3.04	6		<2	7	11	.2	1.3	<.5	69	.02	.114	32	15	.10	103	.010	<1	.78	.003	.05	<1	<1	1.3	<1	.01	5
01675	2.1	22	9	61	.1	22	5	117	2.25	7		<2	4	8	<.2	.9	<.5	26	.01	.052	31	8	.05	52	.007	<1	.44	.003	.03	<1	<1	.9	<1	.01	3
01676	.4	3	3	8	.3	2	<1	13	.20	<1		<2	3	7	<.2	<.5	<.5	5	.02	.014	33	3	.01	34	.004	4	.15	.004	.02	<1	<1	.3	1	<.01	3
01677	7.2	11	15	75	.4	16	2	31	2.12	8		<2	7	25	<.2	4.5	<.5	23	.01	.061	26	4	.01	50	.004	<1	.24	.004	.03	<1	<1	.4	<1	.03	1
01678	1.4	25	12	82	.5	26	7	121	2.89	5		<2	4	23	<.2	<.5	<.5	21	.25	.069	24	16	.25	159	.003	<1	.90	.004	.05	<1	<1	1.3	<1	.01	2
01679	2.1	19	27	43	.7	13	2	67	3.96	29		<2	5	38	<.2	1.0	.5	53	.03	.283	23	15	.05	66	.011	<1	.73	.005	.04	<1	<1	1.1	<1	.03	1
01680	3.2	27	28	55	1.6	21	4	99	6.22	19		<2	6	12	<.2	2.3	<.5	61	.02	.324	20	27	.13	74	.018	<1	.86	.004	.05	<1	<1	1.3	<1	.02	5
RE 01680	3.4	26	28	55	1.8	21	4	100	6.30	19		<2	6	12	<.2	2.2	.6	67	.02	.333	19	26	.13	75	.018	<1	.86	.004	.05	<1	<1	1.4	<1	.02	5
01681	3.1	55	20	85	.3	26	3	182	2.76	23		<2	4	219	<.2	1.8	.6	35	.04	.133	25	10	.01	103	.004	1	.25	.004	.03	<1	<1	1.0	<1	.03	1
01682	1.7	10	6	36	.5	10	2	54	1.13	10		<2	2	29	<.2	.6	<.5	27	.05	.041	25	8	.01	30	.011	1	.15	.004	.02	<1	<1	.4	<1	.01	3
01683	1.3	10	5	24	.1	8	2	34	.97	9		<2	1	14	<.2	<.5	<.5	20	.01	.030	24	5	.01	40	.005	2	.23	.004	.02	<1	<1	.4	<1	<.01	4
01685	1.2	52	12	29	2.9	12	2	39	1.32	17		<2	1	104	.3	<.5	.5	11	.07	.117	17	8	.03	93	.006	1	.48	.004	.04	<1	<1	1.0	<1	.01	3
01686	1.7	92	13	105	.5	48	23	839	3.22	56		<2	4	67	.7	.9	.8	10	.19	.268	29	6	.09	48	.003	<1	.66	.004	.03	<1	1	2.3	1	.01	<1
01687	1.1	23	14	76	.2	26	5	191	2.21	53		<2	4	41	.4	<.5	<.5	28	.17	.072	24	17	.17	63	.026	<1	.51	.005	.05	<1	<1	1.2	1	.02	5
01688	1.2	21	16	74	<.1	36	11	277	4.64	13		<2	2	9	.3	1.2	<.5	53	.07	.124	18	59	.43	73	.009	<1	1.17	.006	.05	<1	<1	2.2	<1	.02	3
01689	1.9	35	17	130	.5	55	17	430	5.84	26		<2	2	21	.4	<.5	<.5	64	.13	.169	18	69	.51	140	.008	<1	1.36	.005	.05	<1	<1	3.0	2	.03	7
01690	2.0	24	66	62	.4	26	6	202	4.15	25		<2	6	12	<.2	1.1	<.5	31	.07	.146	22	28	.23	92	.006	<1	.84	.005	.05	<1	<1	1.5	<1	.02	<1
01691	1.7	40	21	70	<.1	40	10	155	2.90	21		<2	2	8	<.2	1.5	<.5	48	.05	.076	21	26	.18	41	.008	<1	.57	.005	.02	<1	<1	2.0	<1	.01	5
01692	1.2	32	7	82	.3	32	6	82	2.50	15		<2	5	6	<.2	.5	<.5	27	.01	.056	28	4	.02	20	.004	2	.29	.003	.02	<1	<1	.7	<1	<.01	1
01693	1.5	18	14	47	.2	19	5	151	3.85	13		<2	6	7	<.2	.6	<.5	29	.03	.159	25	28	.19	82	.006	<1	.89	.004	.04	<1	<1	1.5	<1	<.01	<1
01695	.8	8	11	32	.7	13	3	90	2.52	13		<2	4	13	<.2	<.5	<.5	22	.05	.147	21	18	.14	69	.008	<1	.61	.003	.03	<1	<1	.8	<1	.01	1
01696	1.3	21	18	62	.2	25	8	278	4.47	16		<2	3	22	<.2	.6	<.5	37	.18	.108	23	29	.30	84	.015	<1	.96	.005	.05	<1	<1	1.4	<1	.02	1
01698	.6	10	11	34	.3	12	4	184	2.07	14		<2	2	11	<.2	<.5	.5	22	.08	.037	23	15	.12	67	.011	<1	.63	.004	.04	<1	<1	.9	<1	.01	3
01699	1.0	14	11	34	.1	15	5	263	2.99	21		<2	7	8	<.2	.7	<.5	34	.06	.036	27	21	.15	74	.027	<1	.86	.004	.05	<1	<1	1.4	<1	<.01	2
01701	.3	5	9	15	.1	5	1	50	1.32	18		<2	7	5	<.2	<.5	<.5	12	.03	.036	33	7	.07	43	.004	1	.54	.003	.05	<1	<1	.5	<1	<.01	4
01702	.3	8	10	32	.1	10	3	111	1.89	29		<2	5	4	<.2	<.5	<.5	16	.02	.040	32	10	.14	50	.002	<1	.71	.004	.06	1	<1	.7	<1	.01	3
STANDARD C3	27.9	69	36	178	5.6	38	12	801	3.42	56		<2	22	30	25.0	17.6	23.3	85	.61	.097	19	181	.65	161	.090	22	1.87	.044	.18	15	2	4.5	2	.03	5
STANDARD G-2	1.6	4	3	45	<.1	8	4	539	2.03	<1		<2	5	74	<.2	<.5	<.5	42	.67	.107	8	84	.63	240	.130	1	.94	.084	.51	2	1	2.6	1	<.01	6

Sample type: SOIL SS80 60C. Samples beginning 'RE' are reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01703	.3	23	23	55	.6	22	10	688	2.83	24	<1	<2	4	29	<.2	<.5	<.5	16	.38	.086	22	15	.23	74	.004	3	.97	.006	.11	1	<1	1.5	2	.02	1
01704	.3	20	22	61	.2	23	11	705	3.18	27	<1	<2	7	23	.2	<.5	.5	17	.28	.056	28	17	.25	83	.005	3	1.02	.006	.09	1	<1	2.0	1	.01	1
01705	.3	20	15	41	.2	15	6	288	2.10	19	<1	<2	1	20	<.2	<.5	.5	16	.25	.058	24	10	.10	86	.006	<1	.63	.005	.08	1	<1	1.0	<1	.01	2
01706	.3	18	15	44	.3	17	7	279	2.66	25	<1	<2	1	7	<.2	<.5	.7	16	.07	.051	25	12	.17	73	.005	1	.77	.004	.08	1	<1	1.0	2	.01	2
01708	.3	25	19	49	.2	21	7	236	2.65	25	1	<2	1	16	.2	<.5	.8	19	.18	.043	24	14	.18	66	.007	<1	.73	.005	.08	1	<1	1.3	1	<.01	2
01709	.4	34	34	79	.7	37	17	966	4.06	27	2	<2	3	30	.3	.6	.6	24	.37	.101	21	23	.28	106	.006	<1	1.31	.007	.12	1	<1	2.7	<1	.03	1
01710	.5	32	30	71	.4	20	15	1169	3.45	16	3	<2	2	15	.2	<.5	.7	28	.12	.107	19	22	.16	88	.011	<1	1.09	.005	.07	<1	<1	1.9	<1	.04	2
01711	.6	11	10	25	<.1	9	3	81	1.56	16	1	<2	2	5	<.2	<.5	<.5	24	.04	.029	26	8	.04	37	.007	<1	.48	.004	.03	1	<1	.7	<1	<.01	3
01712	.3	37	33	79	.6	34	15	744	3.34	15	3	<2	5	36	<.2	<.5	<.5	26	.60	.096	32	25	.40	83	.010	<1	1.27	.006	.08	<1	1	3.3	1	.04	2
01713	.4	28	33	82	.4	28	15	574	3.74	17	2	<2	4	24	<.2	<.5	<.5	30	.26	.063	27	26	.40	118	.008	<1	1.36	.005	.08	1	<1	2.5	1	.02	2
01714	.2	30	33	65	.3	25	14	463	3.62	20	2	<2	5	8	<.2	.7	<.5	28	.08	.061	28	21	.37	68	.007	<1	1.26	.004	.07	1	<1	2.4	<1	.02	2
01715	.6	20	28	46	.2	17	6	259	3.50	28	1	<2	9	4	<.2	.5	<.5	27	.03	.048	29	13	.17	48	.010	<1	.80	.004	.05	1	<1	1.5	<1	<.01	2
01716	.3	14	30	41	.8	14	5	147	3.93	16	1	<2	<1	4	<.2	<.5	2.5	37	.05	.059	19	23	.24	53	.012	1	1.14	.004	.04	1	<1	1.1	<1	.02	3
01717	.7	23	34	64	.4	22	9	232	5.25	24	3	<2	5	5	<.2	.9	<.5	34	.06	.085	20	27	.27	67	.012	<1	1.21	.005	.07	1	<1	1.7	<1	.02	3
01718	.3	12	21	38	.4	12	4	151	3.15	10	1	<2	3	4	.2	<.5	<.5	24	.05	.056	19	18	.23	49	.006	<1	1.03	.004	.05	1	<1	1.2	<1	.02	2
01719	.3	7	17	23	.4	7	3	91	2.35	14	<1	<2	1	5	<.2	<.5	<.5	33	.05	.032	21	14	.16	79	.010	<1	.86	.004	.04	1	<1	.9	<1	.01	4
01720	.3	28	26	60	.1	24	10	216	4.30	25	1	<2	6	4	<.2	.7	<.5	26	.04	.058	26	24	.40	75	.009	<1	1.34	.005	.07	1	<1	1.9	<1	.01	3
01721	.4	15	19	40	.2	13	6	237	3.15	25	<1	<2	4	7	<.2	.8	<.5	30	.08	.044	29	13	.15	78	.012	2	.79	.005	.05	1	<1	1.3	<1	<.01	3
01722	.3	19	24	52	<.1	22	8	197	3.93	19	1	<2	7	7	<.2	.8	<.5	35	.09	.036	26	26	.39	71	.017	1	1.21	.006	.05	1	<1	1.8	<1	.01	2
01723	.6	41	49	61	1.4	34	14	515	3.68	36	2	4	4	19	.3	.9	.6	29	.16	.055	30	21	.24	83	.007	<1	1.23	.005	.06	1	<1	3.5	1	.02	2
01724	.5	39	50	58	.9	36	15	632	3.97	34	5	<2	5	18	.2	1.8	<.5	31	.14	.059	30	22	.25	88	.007	<1	1.26	.005	.06	<1	<1	3.6	<1	.02	2
01725	.6	27	20	68	.2	21	10	266	4.60	22	1	<2	1	4	<.2	.7	<.5	37	.04	.083	20	24	.31	48	.009	<1	1.33	.004	.05	1	<1	1.3	<1	.02	4
RE 01725	.5	26	20	64	.2	21	10	256	4.56	21	1	<2	3	4	<.2	1.1	<.5	33	.04	.082	18	23	.30	48	.009	<1	1.27	.004	.04	<1	<1	1.2	<1	.02	3
01726	.4	12	15	38	.4	14	5	171	3.23	14	<1	<2	6	3	<.2	<.5	<.5	24	.03	.053	22	22	.33	36	.005	<1	1.18	.004	.05	1	<1	1.3	<1	.01	3
01727	.5	19	21	58	.2	17	8	271	4.71	21	1	<2	6	4	<.2	<.5	<.5	36	.04	.059	23	31	.32	53	.011	<1	1.28	.004	.05	1	<1	1.8	<1	.01	5
01728	.2	37	35	63	.4	28	13	321	4.26	34	1	<2	11	6	<.2	<.5	<.5	20	.06	.054	28	19	.31	60	.006	<1	1.23	.004	.06	1	<1	1.9	<1	.01	2
01729	.2	25	23	65	.2	25	9	180	4.13	32	1	<2	5	10	<.2	.7	<.5	20	.12	.061	23	19	.32	59	.005	<1	1.11	.005	.07	2	<1	1.6	<1	.02	2
01730	.6	33	34	48	.1	20	9	196	5.49	48	1	<2	3	8	.2	.8	.6	31	.10	.062	21	17	.13	49	.012	<1	.81	.005	.05	1	<1	1.1	<1	.02	5
01731	.4	33	25	69	.4	31	13	1959	3.49	26	1	<2	7	27	.4	<.5	<.5	22	.38	.074	36	21	.29	78	.005	<1	1.39	.006	.08	<1	<1	3.6	1	.02	2
01732	.5	16	22	45	.4	14	5	164	4.54	30	1	<2	3	4	<.2	1.0	<.5	29	.02	.076	27	19	.17	48	.006	<1	.93	.004	.06	1	<1	.9	<1	.02	3
01733	.3	17	16	47	.6	16	6	170	3.10	26	1	<2	6	4	<.2	<.5	<.5	16	.02	.064	27	16	.22	36	.003	1	.93	.005	.06	1	<1	1.0	<1	.01	3
01734	.4	22	20	60	.3	23	8	302	3.99	32	1	<2	5	4	.2	<.5	<.5	17	.04	.085	25	19	.23	52	.005	<1	1.09	.005	.08	1	<1	1.1	<1	.02	2
01735	.3	15	19	46	.1	15	5	247	3.20	27	1	<2	1	4	.2	<.5	<.5	19	.02	.074	27	16	.18	58	.005	<1	.85	.005	.09	1	<1	.7	<1	.01	4
01736	.3	17	17	47	.1	17	6	222	3.05	28	1	<2	3	4	.2	.8	.7	17	.02	.048	27	15	.20	49	.005	<1	.92	.004	.09	1	<1	1.0	<1	.01	3
STANDARD C3	27.4	71	38	179	5.7	38	12	801	3.43	53	5	<2	23	29	25.2	17.7	23.0	81	.60	.097	18	182	.64	162	.084	21	1.85	.044	.18	15	2	4.5	1	.03	6
STANDARD G-2	1.5	4	2	45	<.1	7	4	522	1.96	<1	3	<2	3	74	<.2	<.5	<.5	39	.63	.098	7	75	.60	228	.125	1	.96	.100	.52	2	<1	2.4	2	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01737	.3	13	19	33	.2	12	5	136	2.98	28	<1	<2	6	4	<.2	<.5	.7	17	.02	.041	26	13	.15	34	.006	3	.69	.004	.07	1	<1	.9	<1	.01	1
01738	.4	22	21	58	.1	21	8	227	3.70	38	<1	<2	7	6	.2	.9	1.1	17	.04	.053	28	16	.22	60	.004	<1	.88	.004	.09	1	<1	1.1	<1	.01	1
01739	.2	14	12	28	.3	10	3	80	1.98	27	<1	<2	4	5	<.2	<.5	.5	16	.04	.027	32	10	.10	68	.005	1	.59	.003	.06	1	<1	.7	<1	<.01	3
01742	1.2	47	50	112	2.0	62	17	433	4.29	54	14	<2	7	76	.6	<.5	1.3	24	1.18	.126	37	26	.27	160	.005	3	2.02	.010	.20	1	1	4.9	<1	.07	1
01743	.5	24	27	73	.1	20	8	385	3.66	32	1	<2	5	20	.2	<.5	.9	25	.19	.058	24	19	.18	122	.006	1	1.18	.006	.12	1	<1	1.7	<1	.01	2
01744	.4	23	23	53	.1	24	8	165	3.28	26	1	<2	7	7	<.2	<.5	.7	24	.06	.038	27	20	.25	66	.006	<1	1.16	.004	.07	1	<1	1.9	<1	.01	2
01745	.4	37	25	83	.5	45	16	841	3.67	23	4	<2	6	35	.2	<.5	<.5	30	.56	.077	28	29	.47	99	.018	3	1.42	.006	.10	<1	1	4.0	<1	.03	2
01746	.3	9	16	33	.1	12	4	134	3.40	22	<1	<2	2	5	.2	.5	.8	24	.04	.064	20	15	.15	40	.007	<1	.75	.003	.04	1	<1	.7	<1	.02	1
01747	.7	12	21	35	.2	15	5	107	4.12	28	1	<2	2	4	<.2	<.5	.8	29	.03	.069	19	20	.19	44	.005	<1	.94	.004	.05	1	<1	.9	<1	.02	1
01748	.9	14	24	36	.2	15	5	108	4.07	31	<1	<2	6	3	.2	.7	.8	31	.03	.066	23	18	.20	48	.006	<1	.91	.003	.05	1	<1	1.2	<1	.02	1
01749	.6	8	18	27	<.1	9	3	80	3.29	23	<1	<2	3	4	<.2	.7	.8	29	.03	.050	26	15	.14	41	.005	<1	.92	.003	.04	1	<1	1.0	<1	.01	2
01750	.8	16	12	30	.1	14	5	147	2.38	53	<1	<2	3	5	<.2	.6	1.4	25	.02	.049	29	7	.04	25	.004	<1	.45	.003	.03	1	<1	.7	<1	<.01	2
01751	.4	41	31	77	<.1	41	18	605	3.85	26	<1	<2	7	9	.2	1.0	<.5	33	.13	.056	34	29	.52	107	.020	2	1.39	.005	.07	1	1	3.5	<1	<.01	3
01752	1.4	39	57	69	.2	44	19	752	4.00	27	<1	<2	8	11	.2	<.5	1.6	37	.17	.062	33	32	.51	100	.022	2	1.49	.005	.08	<1	<1	3.4	<1	.01	3
01753	.4	21	17	61	<.1	25	9	321	3.26	14	1	<2	3	6	<.2	<.5	<.5	36	.10	.067	23	31	.42	89	.014	<1	1.64	.005	.07	<1	1	1.9	<1	.02	4
01754	.4	20	24	49	.2	19	8	278	4.13	24	<1	<2	2	5	.2	.6	<.5	34	.06	.057	23	24	.28	76	.015	1	1.14	.004	.05	1	<1	1.2	<1	.01	3
01755	.2	25	20	61	.2	35	12	275	3.75	15	<1	<2	4	19	.3	.8	<.5	47	.39	.050	23	37	.58	140	.025	1	1.79	.006	.09	1	1	2.9	<1	.01	5
01756	.3	24	21	62	.1	26	11	296	4.25	17	<1	<2	4	6	.2	1.3	<.5	53	.12	.054	23	35	.51	107	.030	<1	1.59	.005	.07	<1	<1	2.6	<1	.02	4
01757	.4	19	18	53	<.1	21	8	267	3.12	14	<1	<2	3	7	<.2	<.5	<.5	42	.17	.046	23	27	.44	126	.020	<1	1.31	.004	.07	1	<1	2.0	<1	.01	5
01758	.2	37	27	76	<.1	43	17	415	3.83	20	<1	<2	6	10	.2	.8	<.5	38	.20	.044	24	31	.52	110	.026	<1	1.61	.005	.10	1	1	3.0	<1	.01	3
01759	.3	9	17	33	.2	11	4	89	2.57	10	<1	<2	1	8	<.2	<.5	<.5	32	.09	.043	21	23	.28	80	.016	1	1.07	.004	.05	<1	<1	1.2	<1	.02	5
01760	.4	9	15	30	.1	11	3	85	2.43	11	<1	<2	1	7	<.2	<.5	<.5	33	.07	.038	21	20	.25	76	.015	<1	1.00	.004	.05	<1	<1	1.2	<1	.02	5
RE 01760	.3	8	14	30	.1	11	3	85	2.43	10	<1	<2	2	5	<.2	<.5	<.5	30	.07	.037	21	19	.24	73	.014	<1	.98	.004	.05	<1	<1	1.2	<1	.02	5
01761	.5	36	28	79	<.1	39	15	416	4.28	24	1	<2	7	20	.2	<.5	<.5	38	.29	.041	27	33	.51	107	.012	<1	1.63	.006	.09	<1	<1	2.9	<1	<.01	4
01762	.5	33	25	71	<.1	34	13	297	4.12	22	1	<2	6	16	.2	<.5	<.5	35	.22	.038	25	30	.46	92	.013	1	1.47	.005	.09	1	<1	2.7	<1	.01	4
01763	.4	40	24	77	.1	39	18	812	3.56	19	<1	<2	8	26	.2	<.5	<.5	33	.42	.071	30	28	.52	115	.035	2	1.24	.006	.09	<1	1	4.1	<1	.01	3
01764	.4	16	18	37	<.1	14	6	105	2.81	21	<1	<2	6	7	<.2	<.5	<.5	28	.07	.025	27	14	.20	59	.008	<1	.99	.004	.06	1	<1	1.6	<1	<.01	4
01765	.5	12	18	36	.1	12	5	157	3.14	22	<1	<2	5	5	<.2	<.5	<.5	30	.05	.041	26	17	.18	56	.017	<1	.85	.004	.05	1	<1	1.3	<1	<.01	3
01766	.7	12	19	37	.2	14	4	166	3.74	18	<1	<2	3	5	<.2	<.5	.5	44	.06	.050	23	22	.20	77	.022	1	1.05	.004	.05	<1	<1	1.5	<1	.01	5
01767	.3	15	19	44	.2	16	5	166	3.08	20	1	<2	4	5	<.2	<.5	<.5	25	.04	.046	24	21	.28	74	.007	1	1.07	.004	.08	1	<1	1.5	<1	.01	4
01768	.3	25	23	61	.3	28	12	746	3.23	25	1	<2	4	19	<.2	<.5	.6	24	.23	.061	25	20	.30	91	.007	<1	1.13	.004	.09	<1	<1	2.3	<1	.01	3
01769	.5	10	17	25	.1	8	3	176	2.81	28	<1	<2	2	4	<.2	<.5	<.5	25	.03	.089	25	10	.07	46	.011	<1	.55	.003	.04	1	<1	.7	<1	.01	3
01770	.4	8	16	22	.1	8	2	106	2.77	23	<1	<2	1	4	<.2	<.5	<.5	21	.03	.063	21	12	.10	37	.005	<1	.67	.003	.04	<1	<1	.4	<1	.01	3
01771	.7	29	28	69	.4	35	17	1661	3.46	22	5	<2	4	38	.4	<.5	<.5	27	.60	.092	23	21	.38	96	.012	2	1.22	.006	.09	1	<1	2.9	<1	.04	2
STANDARD C3	27.2	69	36	177	5.4	38	12	811	3.38	58	23	<2	22	30	24.9	15.5	22.7	85	.61	.095	19	182	.65	160	.095	23	1.86	.043	.18	16	2	4.6	1	.03	6
STANDARD G-2	1.5	4	2	45	<.1	8	4	547	2.05	1	2	<2	3	75	<.2	<.5	<.5	43	.67	.102	8	81	.62	231	.135	2	.95	.082	.51	2	1	2.7	<1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01772	.7	20	26	77	.3	24	10	362	3.54	39	1	<2	3	20	.2	<.5	1.0	21	.24	.064	20	17	.22	82	.006	4	1.05	.006	.09	1	<1	1.5	<1	.02	2
01773	.5	12	16	22	.2	8	2	55	1.84	21	<1	<2	2	8	<.2	<.5	.8	14	.08	.039	20	8	.09	86	.004	<1	.61	.003	.05	<1	<1	.6	<1	.02	3
01774	.8	37	44	92	.6	41	25	829	4.55	33	2	<2	6	34	.4	<.5	1.3	25	.41	.082	22	24	.25	118	.006	3	1.59	.006	.12	1	1	3.4	<1	.03	3
01776	.8	48	35	108	.9	52	18	864	4.59	128	5	<2	6	31	.7	.6	1.5	23	.44	.111	25	28	.27	144	.006	3	1.72	.007	.15	1	1	4.4	1	.03	3
01777	.7	45	33	105	1.6	49	17	769	4.42	133	4	<2	6	36	.9	<.5	1.3	21	.50	.112	24	25	.26	143	.006	1	1.64	.006	.15	1	1	4.0	1	.03	3
01778	.5	36	31	85	.9	38	13	705	3.89	60	2	<2	3	24	.4	<.5	1.1	23	.29	.076	24	20	.17	101	.005	2	1.32	.005	.13	1	1	2.5	<1	.03	2
01779	.5	47	31	95	.7	61	17	959	3.98	44	3	<2	6	33	.6	<.5	.9	16	.46	.085	30	22	.23	141	.005	<1	1.62	.005	.15	1	1	4.3	2	.03	2
01780	.3	12	12	28	.1	10	4	98	1.76	19	<1	<2	2	6	<.2	<.5	<.5	13	.04	.033	29	9	.11	84	.003	<1	.69	.002	.06	1	<1	.8	<1	<.01	3
01781	.2	30	23	71	.1	31	10	307	3.89	39	1	<2	9	5	<.2	.8	.5	15	.03	.032	34	19	.31	76	.003	3	1.11	.004	.09	1	<1	1.6	<1	<.01	2
01782	.2	33	23	65	.1	25	10	297	3.84	39	1	<2	3	5	<.2	<.5	.7	18	.03	.048	28	15	.19	71	.005	3	.95	.003	.08	1	<1	1.5	<1	.01	2
01783	.2	35	32	72	.4	30	16	778	3.84	34	1	<2	7	23	.2	<.5	.9	21	.30	.080	25	18	.27	83	.005	2	1.23	.005	.09	1	1	2.8	<1	.02	2
01784	.6	77	37	87	1.4	53	18	1854	4.32	31	4	<2	5	55	.3	<.5	.9	23	.92	.215	33	27	.26	108	.010	1	1.81	.006	.11	1	<1	4.9	<1	.10	2
01785	.4	44	21	52	.4	29	9	342	3.32	31	2	<2	3	31	.2	<.5	.7	20	.52	.071	25	15	.16	40	.008	2	.86	.003	.05	1	<1	1.7	<1	.02	1
RE 01785	.3	43	21	53	.4	29	9	341	3.29	31	2	<2	3	31	.3	<.5	.6	18	.52	.071	25	14	.16	40	.008	2	.85	.003	.05	2	<1	1.7	1	.03	2
01786	.3	48	22	72	1.1	39	14	1016	3.57	26	4	<2	6	38	.3	<.5	.6	23	.61	.137	34	25	.34	91	.006	1	1.62	.006	.09	1	1	4.0	<1	.05	2
01787	.7	27	22	74	.2	22	9	197	4.92	30	1	<2	7	8	<.2	.8	.7	30	.07	.055	27	20	.24	81	.015	<1	1.13	.003	.07	1	<1	1.8	<1	.01	3
01788	.3	21	15	50	.4	18	9	779	2.71	23	1	<2	3	34	<.2	<.5	<.5	22	.51	.074	24	18	.26	61	.005	1	1.16	.004	.07	1	<1	1.6	1	.02	4
01789	.3	7	8	17	.2	6	2	53	1.26	13	<1	<2	3	8	<.2	<.5	<.5	15	.05	.035	28	7	.06	45	.004	2	.51	.002	.03	<1	<1	.5	<1	<.01	5
01790	.3	9	13	24	.3	7	3	86	1.81	16	<1	<2	2	6	<.2	<.5	<.5	23	.06	.035	28	10	.14	32	.006	<1	.71	.004	.04	<1	<1	.9	1	.01	4
01901	2.1	24	13	63	.5	19	3	117	4.26	6	1	<2	4	6	<.2	.7	.8	37	.01	.055	21	24	.29	104	.013	1	1.28	.002	.04	<1	1	1.3	<1	.02	4
01902	2.4	21	15	55	1.1	17	3	142	4.28	7	1	<2	5	8	<.2	1.4	.5	48	.02	.107	20	27	.21	132	.017	<1	1.07	.001	.04	<1	<1	1.4	<1	.02	3
01903	.9	4	2	13	.1	4	1	65	.59	<1	<1	<2	2	4	<.2	<.5	<.5	11	.01	.027	21	4	.02	43	.004	<1	.33	.002	.02	<1	<1	.4	<1	<.01	5
01904	2.3	19	15	58	.1	17	4	137	4.63	9	1	<2	7	8	<.2	.7	<.5	35	.06	.132	22	20	.20	147	.016	2	.87	.002	.06	<1	<1	1.3	<1	.01	3
01905	1.6	12	6	28	.1	9	2	62	1.25	2	<1	<2	1	5	<.2	<.5	<.5	17	.05	.032	23	6	.03	58	.007	1	.33	.002	.03	<1	<1	.3	<1	<.01	3
01906	1.0	13	4	39	.1	12	4	204	1.60	4	<1	<2	1	8	<.2	<.5	<.5	13	.10	.043	22	6	.08	92	.004	<1	.34	.003	.04	<1	<1	.5	<1	<.01	2
01907	1.5	20	12	66	.4	21	6	140	2.89	6	1	<2	4	13	<.2	<.5	<.5	20	.20	.055	21	18	.33	187	.005	<1	1.06	.004	.06	<1	<1	1.4	<1	.01	1
01908	.6	27	6	28	<.1	8	1	22	2.22	79	<1	<2	8	7	.2	2.0	<.5	21	.04	.048	27	7	.02	43	.001	<1	.48	.002	.03	<1	<1	.5	<1	<.01	1
01909	1.6	37	13	70	.1	15	5	449	4.08	5	1	<2	3	25	<.2	.7	<.5	27	.23	.127	18	14	.16	156	.007	1	.80	.002	.05	<1	<1	.9	<1	.03	1
01910	1.3	27	19	40	.5	17	7	489	1.84	5	1	<2	<1	24	.2	<.5	<.5	24	.27	.071	18	13	.14	202	.007	1	.73	.003	.05	<1	<1	.9	<1	.02	3
01911	.8	21	7	41	.4	16	4	128	1.99	8	1	<2	1	8	<.2	<.5	<.5	17	.09	.059	19	12	.16	111	.004	<1	.64	.003	.05	<1	<1	.6	<1	.01	2
01912	1.1	28	12	54	.7	26	6	235	3.62	19	1	4	2	8	<.2	.5	<.5	29	.10	.122	17	23	.14	99	.010	<1	.63	.002	.04	<1	<1	1.1	<1	.01	2
01914	1.8	34	16	80	.1	32	9	188	4.10	19	2	<2	5	14	<.2	.9	.8	25	.18	.088	21	13	.07	126	.015	<1	.51	.003	.04	<1	<1	1.4	<1	.02	1
01915	1.3	25	16	62	.1	22	6	145	3.90	7	1	<2	7	7	<.2	.9	.7	25	.06	.086	22	18	.18	104	.008	<1	.90	.002	.05	<1	<1	1.3	<1	.01	2
01916	1.5	67	4	73	.3	149	30	218	5.02	3	<1	<2	4	6	<.2	1.3	<.5	46	.04	.131	19	121	.33	77	.002	<1	1.36	.003	.02	<1	<1	4.3	<1	.01	4
STANDARD C3	27.1	66	36	172	5.6	37	12	784	3.33	56	24	<2	21	28	25.0	16.0	23.6	81	.59	.097	18	174	.62	158	.088	20	1.86	.040	.16	17	2	4.3	1	.03	6
STANDARD G-2	1.6	4	3	49	<.1	8	4	536	2.03	<1	2	<2	4	72	<.2	<.5	<.5	43	.65	.106	8	79	.62	233	.131	4	.97	.079	.51	2	1	2.6	<1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01918	1.8	19	15	61	.1	22	7	388	4.32	14	1	<2	5	7	.2	1.0	<.5	34	.05	.209	29	26	.26	125	.008	3	.87	.004	.07	<1	<1	1.5	<1	.01	2
01919	1.0	20	13	47	.5	26	8	313	3.20	15	1	<2	2	11	.2	.5	<.5	32	.10	.238	22	40	.26	94	.006	2	.76	.003	.06	<1	<1	1.6	<1	.01	1
01920	1.0	37	30	91	.7	47	14	486	3.57	46	1	<2	3	11	.5	.8	2.3	39	.09	.078	30	43	.36	83	.009	2	1.00	.005	.06	<1	1	3.0	<1	<.01	2
01921	1.4	15	32	45	1.2	18	5	102	3.96	27	1	<2	5	7	.2	.8	.6	51	.03	.169	25	36	.17	63	.011	1	.89	.003	.04	<1	<1	1.7	<1	.01	2
01922	1.3	7	5	40	.4	10	2	33	1.05	7	<1	<2	3	6	<.2	.7	<.5	15	.04	.030	34	6	.01	29	.003	3	.17	.002	.02	<1	<1	.4	<1	<.01	3
01925	1.4	14	15	67	.9	18	5	116	3.34	19	1	<2	4	10	<.2	1.0	<.5	31	.05	.118	27	16	.15	54	.010	1	.78	.003	.04	<1	<1	1.4	<1	.02	2
01926	.7	8	13	31	.1	9	3	159	2.32	22	<1	<2	3	10	.2	.6	<.5	32	.09	.147	28	13	.11	151	.017	3	.58	.004	.05	1	<1	1.1	<1	.01	3
02001	5.1	27	16	70	<.1	21	4	120	6.49	23	1	<2	5	11	<.2	1.5	.5	51	.03	.121	35	24	.20	89	.015	1	1.00	.004	.03	<1	1	1.0	<1	.03	7
02002	1.6	12	7	30	.1	19	4	140	2.24	17	<1	<2	1	5	<.2	<.5	<.5	28	.02	.058	21	16	.09	88	.004	<1	.62	.003	.03	<1	<1	.5	<1	.01	5
02004	2.0	33	18	85	<.1	32	8	320	4.05	11	2	<2	8	7	<.2	1.3	<.5	16	.01	.052	31	16	.27	98	.003	3	1.00	.003	.09	<1	<1	1.4	<1	.01	1
02005	3.4	38	25	70	.4	26	6	122	7.36	13	1	<2	4	8	<.2	1.6	<.5	38	.02	.083	18	24	.14	90	.015	<1	.91	.003	.05	<1	1	1.3	<1	.02	6
02006	2.7	22	20	68	1.5	20	4	133	3.99	13	1	<2	2	16	<.2	1.8	<.5	60	.08	.129	17	34	.25	93	.039	1	1.34	.007	.05	<1	<1	1.7	<1	.04	5
02007	17.1	25	108	41	1.0	12	2	151	5.23	72	2	<2	2	194	.4	2.8	1.0	44	.03	.596	15	27	.09	299	.009	4	1.00	.017	.23	<1	<1	1.2	<1	.44	2
02008	1.7	21	17	60	.4	26	6	243	4.05	11	1	<2	8	10	<.2	1.1	<.5	27	.03	.110	28	29	.24	80	.008	1	1.13	.003	.07	<1	<1	1.5	<1	.02	2
02009	2.7	22	18	62	.4	20	5	150	4.56	9	1	<2	6	9	<.2	1.1	<.5	38	.02	.093	26	24	.26	116	.011	1	1.00	.004	.07	<1	<1	1.3	<1	.02	3
02015	3.9	36	42	62	.5	20	4	104	5.20	30	2	<2	8	36	<.2	3.5	.5	54	.02	.228	31	21	.09	115	.006	1	.91	.004	.07	<1	<1	1.6	<1	.03	5
02016	9.6	87	64	61	3.0	28	4	115	7.53	368	1	<2	6	85	.5	2.7	3.1	72	.05	.862	21	31	.06	223	.008	2	.92	.005	.08	<1	1	2.4	<1	.06	8
02017	3.2	19	32	49	1.0	15	3	65	3.30	42	1	<2	7	9	.2	.9	.6	38	.02	.196	33	13	.04	53	.009	2	.65	.004	.03	<1	<1	1.0	<1	.02	3
02018	3.8	44	22	117	.5	23	4	50	2.70	126	1	<2	7	19	.6	.6	1.5	31	.02	.148	39	6	.01	60	.002	4	.31	.003	.05	<1	<1	1.8	<1	.03	2
02019	1.0	5	7	26	.1	4	1	29	.50	8	<1	<2	8	8	<.2	<.5	<.5	12	.05	.017	44	3	.01	29	.002	5	.18	.001	.03	<1	<1	.4	1	<.01	3
02020	2.0	24	23	68	.4	25	5	105	4.81	43	2	<2	5	13	.2	1.3	.7	35	.02	.259	27	22	.10	69	.005	<1	.74	.002	.05	<1	<1	1.2	<1	.02	3
RE 02020	2.1	26	23	72	.4	25	5	108	4.91	45	2	<2	5	13	<.2	1.4	1.0	35	.02	.268	28	22	.10	70	.005	3	.76	.003	.05	<1	<1	1.1	<1	.02	3
02021	2.0	24	19	54	.8	20	4	100	4.84	20	1	<2	7	8	<.2	1.6	.5	31	.02	.109	26	23	.12	99	.008	<1	.85	.003	.05	4	<1	1.3	<1	.02	3
02022	1.7	27	9	61	.5	24	6	93	2.60	18	1	<2	6	6	<.2	<.5	<.5	32	.01	.076	32	9	.04	48	.006	2	.41	.003	.03	<1	<1	1.0	<1	.01	3
02024	1.5	16	20	41	.5	16	3	64	3.39	23	1	<2	6	13	<.2	.6	.8	48	.01	.259	26	16	.08	84	.004	3	.74	.003	.05	<1	<1	1.1	<1	.02	3
02025	.6	7	15	18	.5	5	1	33	2.49	8	1	<2	6	7	<.2	.5	<.5	20	.03	.064	27	10	.04	67	.012	2	.47	.002	.02	<1	<1	.7	<1	.02	2
02026	.8	12	11	42	.1	13	5	139	2.58	27	1	<2	2	22	<.2	<.5	1.2	22	.15	.043	34	11	.12	89	.011	2	.63	.003	.04	1	<1	.9	<1	<.01	4
02027	1.3	19	24	53	.1	21	6	177	4.12	19	1	<2	7	9	<.2	<.5	<.5	39	.03	.185	30	30	.20	60	.010	2	.80	.002	.05	<1	<1	1.5	<1	.01	4
02028	1.4	45	51	115	.3	60	22	2500	4.46	35	2	<2	5	32	.4	1.3	1.0	34	.21	.081	25	32	.33	139	.005	2	1.44	.005	.11	<1	<1	2.9	<1	.02	4
02032	1.8	14	13	47	.4	15	4	82	1.85	8	1	<2	7	15	<.2	1.1	<.5	14	.01	.049	39	6	.07	118	.001	2	.90	.005	.04	<1	<1	.6	<1	.01	4
02033	1.0	3	9	11	.3	3	<1	38	1.19	4	<1	<2	4	4	<.2	<.5	<.5	19	.02	.044	28	9	.07	91	.005	<1	.63	.002	.04	<1	<1	.5	<1	<.01	4
02035	1.6	15	15	43	.2	16	4	123	3.96	12	2	<2	3	4	<.2	1.3	<.5	22	.03	.070	18	16	.18	43	.003	2	.76	.003	.05	<1	<1	.5	<1	.03	2
02036	1.5	14	13	42	.1	12	3	123	4.08	8	1	<2	6	4	<.2	.7	<.5	17	.01	.072	27	14	.15	47	.003	2	.74	.004	.04	<1	<1	.6	<1	.02	3
02037	.4	1	2	4	<.1	2	<1	14	.17	1	<1	<2	7	3	<.2	.5	<.5	3	.01	.010	40	3	.01	39	.004	2	.20	.002	.02	<1	<1	.2	1	<.01	4
STANDARD C3	26.9	68	35	174	5.4	37	12	783	3.36	57	23	<2	23	31	25.3	14.7	23.1	84	.61	.097	20	179	.63	165	.094	21	1.80	.044	.19	14	2	4.6	2	.03	6
STANDARD G-2	1.6	4	3	46	<.1	7	4	552	2.07	<1	2	<2	4	79	<.2	<.5	<.5	44	.71	.102	9	80	.62	233	.134	1	.92	.086	.51	2	1	2.9	<1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
02038	1.3	16	18	43	.6	19	4	127	4.72	9	1	<2	2	7	.2	1.7	<.5	39	.02	.145	19	22	.16	41	.008	2	.74	.004	.04	<1	<1	.6	<1	.02	<1
02039	2.0	19	22	47	.1	17	4	178	4.66	11	1	<2	1	7	<.2	1.5	<.5	45	.03	.122	18	24	.17	73	.010	1	.96	.006	.04	<1	<1	.6	<1	.03	1
02041	1.5	26	16	49	.5	22	6	115	3.58	17	1	<2	4	15	<.2	1.4	.8	45	.01	.122	24	12	.05	33	.010	1	.46	.004	.04	<1	<1	.9	<1	.02	2
02044	3.4	24	32	57	.4	20	4	83	6.57	33	1	<2	5	17	.2	2.9	.9	65	.03	.255	19	27	.11	80	.015	1	1.04	.006	.05	<1	<1	1.4	<1	.03	5
02046	4.3	26	41	44	2.0	16	3	78	6.00	32	1	<2	2	46	.2	6.6	2.7	77	.05	.326	13	26	.09	107	.011	3	.87	.007	.06	<1	<1	1.0	<1	.07	3
02049	63.7	83	35	39	.5	25	5	144	3.25	126	2	<2	1	89	.5	3.7	17.9	40	.04	.129	21	9	.02	47	.007	2	.37	.005	.03	1	<1	1.2	<1	.02	1
02050	3.7	28	15	56	.9	12	2	33	2.02	28	1	<2	3	31	<.2	.9	<.5	19	.02	.092	22	7	.02	60	.004	2	.41	.006	.03	<1	<1	.6	<1	.03	<1
RE 02050	3.5	28	15	56	.9	11	2	34	2.03	27	1	<2	3	30	<.2	1.0	<.5	21	.02	.088	20	6	.02	57	.004	2	.41	.004	.03	<1	<1	.5	<1	.03	<1
02051	3.9	19	18	49	.5	14	2	40	1.96	20	<1	<2	2	8	<.2	1.8	<.5	25	.02	.092	25	5	.01	29	.005	<1	.33	.002	.02	<1	<1	.3	<1	.01	1
02052	1.9	27	20	62	.5	27	5	143	4.93	18	1	<2	5	6	.2	1.9	.8	39	.02	.208	23	21	.12	57	.013	<1	.73	.002	.04	<1	<1	1.5	<1	.01	1
02054	.8	16	9	35	.6	11	2	46	1.16	5	<1	<2	3	5	<.2	.8	<.5	18	.01	.023	27	3	.01	20	.005	4	.17	.002	.02	<1	<1	.3	<1	<.01	3
02056	1.1	33	14	119	.3	39	8	169	5.94	21	<1	<2	5	11	.2	1.4	<.5	11	.06	.079	24	14	.13	43	.002	<1	.89	.005	.03	<1	<1	1.1	<1	.01	<1
STANDARD C3	26.2	66	36	166	5.8	39	12	774	3.44	59	24	<2	21	29	24.5	18.1	23.2	84	.59	.098	18	172	.64	155	.088	23	1.91	.049	.17	15	2	4.5	1	.03	6
STANDARD G-2	1.5	2	3	44	<.1	8	4	528	2.08	<1	2	<2	4	85	<.2	<.5	<.5	43	.69	.105	7	77	.62	241	.133	<1	1.07	.085	.55	2	1	2.6	<1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ___

ACME (\LYTICAL LABORATORIES LTD. 852 E. HASTINGS ST (\NCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(6 (?53-1716
(O 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004434R Page 1

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: R. Hall

SAMPLE#	Au* ppb
00658	27.0
00659	7.5
00660	16.5
00661	60.9
00662	20.8
00664	4.9
00665	4.3
00666	12.4
00667	70.2
00668	7.6
00669	13.5
00670	7.3
RE 00670	9.8
00671	2.3
00672	14.2
00673	3.9
00674	8.1
00675	136.9
00677	240.9
00678	128.1
00679	626.3
00680	785.2
00681	108.2
00682	5.6
00683	2.3
00684	2.7
00685	7.0
00686	2.6
00687	2.1
00688	36.2
00689	1.3
00690	.7
00691	9.2
00692	6.4
STANDARD DS2	191.3

AU* BY ACID LEACHED, ANALYSIS BY ICP/MS. (10 gm)
- SAMPLE TYPE: SOIL PULP
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: NOV 16 2000 DATE REPORT MAILED: Nov 24/00 SIGNED BY. C. Toye D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au* ppb
00694	4.8
00695	4.5
00696	.5
00697	<.2
00698	3.9
00699	10.6
00700	1.6
00839	4.1
00840	4.8
00841	68.6
00842	49.7
00843	4.1
00844	5.5
00845	5.6
RE 00845	12.4
00846	4.2
00847	48.3
00848	2.1
00849	5.1
00850	7.8
00851	8.4
00852	15.2
00854	5.8
00855	8.5
00857	13.0
00858	32.0
00860	4.5
00861	2.3
00862	4.1
00863	34.6
00864	22.1
00865	16.7
00866	15.9
00867	2.6
STANDARD DS2	197.7

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au* ppb
00868	11.9
00869	5.5
00870	3.5
00871	12.7
00872	11.6
00873	12.0
00874	10.1
00876	7.0
00877	8.8
00878	7.0
00879	13.3
00880	8.5
00881	15.1
00882	10.0
01001	4.0
01002	10.5
01003	5.4
01004	7.6
01005	37.3
RE 01005	11.7
01006	8.6
01007	8.0
01008	7.5
01009	38.0
01010	9.2
01011	9.0
01300	28.9
01301	19.3
01302	10.0
01303	23.4
01304	18.5
01305	10.5
01306	15.0
01307	5.0
STANDARD DS2	198.4

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ___

SAMPLE#	Au* ppb
01308	7.0
01309	5.9
01310	4.2
01311	11.7
01312	5.3
01313	5.3
01314	3.6
01315	12.5
01317	488.2
01318	181.3
01319	55.2
01320	86.8
01321	4.8
01322	3.9
01323	31.9
01324	42.7
01325	229.9
RE 01325	103.5
01327	282.4
01328	5.6
01329	2.2
01330	5.7
01331	9.6
01332	107.5
01333	166.5
01334	52.0
01336	372.5
01337	66.7
01338	33.2
01339	13.3
01340	6.8
01341	6.2
01342	4.1
01343	11.4
STANDARD DS2	200.3

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ___

SAMPLE#	Au* ppb
01344	4.3
01345	2.9
01346	3.9
01347	1.7
01348	40.6
01349	5.8
01350	2.6
01351	1.1
01352	1.4
01353	3.9
01354	2.2
01355	3.4
01356	5.9
01357	5.7
01358	30.6
01359	6.8
01360	2.3
01361	2.6
01362	3.2
01363	2.6
01364	3.8
01369	99.7
01370	16.2
01371	4.8
RE 01371	13.0
01465	22.9
01466	19.0
01467	7.3
01468	9.6
01469	38.5
01470	48.4
01471	10.4
01473	33.0
01474	8.5
STANDARD DS2	190.0

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA

SAMPLE#	Au* ppb
01475	26.0
01476	26.7
01477	15.4
01478	24.6
01479	11.2
01480	7.2
01481	9.7
01482	2.0
01483	26.7
01484	27.3
01485	8.2
01486	.2
01487	82.9
01490	263.6
01491	8.2
01493	74.8
01494	9.8
01496	126.9
01498	3.1
01499	2.7
01500	3.1
RE 01502	23.3
01501	45.7
01502	8.7
01503	73.4
01504	9.0
01505	20.8
01506	78.4
01507	23.8
01508	1.0
01509	5.5
01510	3.9
01511	3.8
01512	3.5
STANDARD DS2	190.2

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA ___

SAMPLE#	Au* ppb
01513	25.8
01514	19.6
01515	16.1
01516	14.9
01517	115.8
01518	12.0
01519	11.8
01520	4.8
01521	9.8
01522	14.3
01524	45.8
01525	6.4
RE 01525	5.4
01526	47.2
01527	37.4
01528	41.0
01530	105.6
01531	11.7
01533	5.5
01534	10.7
01535	6.8
01536	10.5
01537	63.1
01538	7.7
01539	5.2
01540	37.6
01541	14.6
01542	316.5
01543	45.6
01544	2.8
01545	118.4
01546	72.1
01547	89.8
01548	45.8
STANDARD DS2	196.0

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ___

SAMPLE#	Au* ppb
01549	40.3
01550	2.8
01551	3.7
01552	22.2
01553	10.5
01554	40.3
01555	61.9
01556	40.6
01557	25.8
01558	20.6
01559	11.1
01560	14.8
01561	12.8
01562	6.4
01563	6.0
01564	2.9
01565	3.0
RE 01565	8.4
01566	9.1
01567	28.0
01568	8.1
01569	46.5
01570	12.4
01572	26.5
01573	132.4
01574	12.2
01575	10.9
01576	48.4
01577	21.7
01578	12.5
01579	5.4
01580	7.4
01581	21.7
01582	17.6
STANDARD DS2	189.5

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ___

SAMPLE#	Au* ppb
01583	283.1
01584	38.6
01585	70.3
01586	49.3
01587	71.3
01588	2.1
01589	7.0
01590	1.8
01591	21.2
01592	2.7
01593	4.1
01594	6.6
01595	14.7
RE 01595	19.0
01596	2.3
01597	10.3
01598	27.0
01599	24.1
01600	23.9
01622	3.8
01623	15.5
01624	2.1
01625	1.8
01626	2.5
01627	2.9
01628	1.3
01629	.7
01630	.9
01631	1.2
01632	1.3
01633	1.1
01635	3.9
01636	2.4
01637	5.7
STANDARD DS2	189.3

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

'Data FA

SAMPLE#	Au* ppb
01638	4.9
01639	2.8
01641	256.9
01644	817.9
01670	4.7
01671	2.7
01672	7.8
01673	2.4
01674	1.9
01675	1.4
01676	3.0
01677	1.8
01678	11.4
01679	16.3
01680	6.2
RE 01680	5.5
01681	3.7
01682	6.3
01683	4.9
01685	522.7
01686	56.4
01687	73.3
01688	9.1
01689	7.1
01690	160.9
01691	11.3
01692	9.8
01693	12.9
01695	35.5
01696	7.3
01698	184.7
01699	51.8
01701	16.4
01702	38.2
STANDARD DS2	195.2

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ___

SAMPLE#	Au* ppb
01703	234.4
01704	105.6
01705	67.5
01706	42.9
01708	79.5
01709	62.3
01710	23.5
01711	67.5
01712	8.7
01713	4.6
01714	8.6
01715	16.2
01716	21.0
01717	15.4
01718	3.5
01719	1.4
01720	43.5
01721	13.0
01722	2.4
01723	348.7
01724	106.7
01725	5.8
RE 01725	24.5
01726	38.5
01727	11.1
01728	20.0
01729	22.4
01730	66.7
01731	8.5
01732	12.4
01733	67.4
01734	74.5
01735	46.3
01736	69.2
STANDARD DS2	197.9

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ____

SAMPLE#	Au* ppb
01737	31.4
01738	62.9
01739	32.5
01742	62.4
01743	260.0
01744	21.7
01745	14.5
01746	35.6
01747	31.9
01748	60.1
01749	92.5
01750	216.6
01751	20.2
01752	17.3
01753	5.8
01754	15.8
01755	5.1
01756	1.2
01757	4.6
01758	29.1
01759	1.4
01760	3.0
RE 01760	1.0
01761	4.7
01762	9.0
01763	6.0
01764	39.1
01765	10.0
01766	51.7
01767	23.9
01768	16.8
01769	21.8
01770	32.3
01771	39.6
STANDARD DS2	190.6

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au* ppb
01772	149.7
01773	69.4
01774	84.1
01776	65.5
01777	80.0
01778	17.5
01779	34.1
01780	59.4
01781	57.0
01782	40.7
01783	45.5
01784	25.5
01785	71.4
RE 01785	14.1
01786	92.0
01787	18.3
01788	10.3
01789	48.6
01790	9.6
01901	1.4
01902	1.8
01903	.8
01904	3.0
01905	1.3
01906	4.9
01907	11.9
01908	.9
01909	47.2
01910	2.4
01911	7.7
01912	3.1
01914	21.3
01915	2.1
01916	1.6
STANDARD DS2	192.0

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ___

SAMPLE#	Au* ppb
01918	5.0
01919	9.6
01920	39.0
01921	35.1
01922	92.7
01925	35.9
01926	58.7
02001	2.3
02002	6.1
02004	2.8
02005	6.5
02006	1.1
02007	46.7
02008	1.4
02009	3.5
02015	44.6
02016	54.1
02017	28.7
02018	289.5
02019	30.5
02020	31.3
RE 02020	29.0
02021	15.0
02022	17.4
02024	20.0
02025	6.6
02026	199.9
02027	39.1
02028	76.9
02032	3.5
02033	2.6
02035	7.3
02036	36.9
02037	3.2
STANDARD DS2	193.0

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ___

SAMPLE#	Au* ppb
02038	13.4
02039	5.2
02041	4.7
02044	8.5
02046	243.0
02049	321.8
02050	47.6
RE 02050	52.6
02051	18.6
02052	5.6
02054	5.7
02056	3.8
STANDARD DS2	191.0

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004440 Page 1

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: R. Hall

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00742	.8	17	10	22	.4	8	1	43	2.19	13	<1	<2	1	9	.2	.7	.6	17	.05	.170	22	12	.05	32	.005	3	.43	.003	.02	1	<1	.3	<1	.02	2
00743	1.0	26	10	73	.1	22	5	194	2.17	15	<1	<2	2	19	.3	.9	<.5	22	.13	.059	31	9	.06	51	.010	1	.27	.002	.03	1	<1	.8	<1	.01	2
00744	1.0	18	13	55	.7	16	3	193	2.93	16	<1	<2	2	8	.4	.7	.5	15	.09	.221	25	10	.06	58	.003	1	.38	.003	.03	1	<1	.6	<1	.02	2
00745	2.4	23	17	74	1.2	27	7	391	4.60	57	1	<2	2	10	.6	2.0	3.7	34	.05	.308	21	16	.09	76	.007	1	.62	.003	.03	1	<1	1.2	<1	.03	3
00746	4.6	45	34	79	1.7	47	9	298	5.50	154	1	<2	4	15	.7	6.4	61.0	29	.06	.267	24	21	.14	76	.004	1	.64	.002	.04	1	<1	1.4	1	.03	4
00747	1.0	10	3	23	.2	10	3	110	1.07	19	<1	<2	2	5	<.2	.6	<.5	11	.06	.034	31	5	.03	33	.004	3	.25	.003	.02	1	<1	.6	<1	<.01	3
00748	1.1	15	10	53	.3	18	7	1029	2.48	12	1	<2	3	10	.3	<.5	<.5	32	.18	.078	29	15	.10	89	.016	1	.53	.003	.04	1	<1	1.1	<1	.01	3
00749	1.1	21	11	46	.8	17	6	438	2.72	16	<1	<2	2	6	.4	.7	<.5	24	.04	.134	25	18	.10	56	.011	<1	.59	.002	.04	1	<1	.7	<1	.01	3
00801	1.2	11	8	30	1.2	11	2	78	1.28	2	<1	<2	1	3	<.2	<.5	<.5	15	.02	.048	23	7	.03	30	.005	2	.30	.003	.02	1	<1	.4	<1	<.01	3
00802	.6	32	14	116	.5	41	14	1696	3.53	16	2	<2	2	33	.9	<.5	.7	32	.55	.089	23	30	.29	146	.012	1	1.06	.003	.06	1	<1	2.2	<1	.03	4
00803	.6	21	7	44	.6	17	5	176	2.28	9	1	<2	1	5	.3	.7	<.5	24	.07	.102	22	21	.17	49	.008	1	.77	.002	.03	1	<1	.7	<1	.02	3
00805	.7	21	14	53	.4	25	9	319	3.03	14	1	<2	2	25	.4	<.5	1.0	33	.40	.049	24	21	.24	80	.010	3	.85	.004	.05	1	<1	1.6	<1	.02	4
00806	.8	30	15	86	.3	48	15	903	3.95	22	2	<2	2	16	.7	.6	1.4	30	.20	.091	25	24	.22	71	.012	<1	.85	.004	.05	1	<1	1.5	<1	.02	3
00807	.8	26	20	61	.5	49	9	370	4.32	22	1	<2	2	13	.4	.9	1.0	27	.15	.099	23	23	.20	46	.012	2	.70	.003	.05	1	<1	1.2	<1	.02	3
00808	.6	10	15	34	.8	12	4	254	2.16	9	1	<2	1	6	.2	.7	<.5	15	.05	.122	23	11	.12	75	.004	<1	.51	.002	.04	1	<1	.4	<1	.02	2
00809	.7	16	15	45	.5	20	5	147	3.11	15	1	<2	3	6	.4	.9	.6	20	.08	.079	21	20	.25	63	.013	<1	.77	.003	.04	1	<1	1.0	<1	.02	2
00810	.4	3	5	10	.1	3	1	21	.62	2	<1	<2	8	3	<.2	<.5	<.5	7	.03	.035	35	5	.04	33	.002	<1	.58	.002	.03	<1	<1	.5	<1	<.01	3
00811	.4	31	16	47	1.3	63	8	1577	1.95	9	13	<2	1	240	.5	<.5	.9	11	3.48	.147	7	15	.62	116	.007	11	.77	.009	.08	<1	<1	1.9	<1	.22	2
00813	1.1	11	15	31	1.1	11	2	108	3.18	11	1	<2	1	5	.4	<.5	<.5	18	.03	.097	19	15	.14	43	.006	<1	.64	.002	.03	1	<1	.4	<1	.03	3
00814	1.1	7	12	24	.6	7	1	167	1.97	6	<1	<2	2	5	.2	.6	<.5	18	.04	.070	21	12	.12	75	.006	2	.57	.002	.03	1	<1	.4	<1	.02	2
00815	1.9	19	13	49	2.2	18	4	173	2.37	10	1	<2	3	9	.3	1.0	<.5	18	.04	.055	23	16	.23	136	.007	<1	.68	.001	.04	1	<1	.9	<1	.02	2
00816	1.0	8	14	16	1.1	6	1	82	1.82	8	<1	<2	1	6	.2	<.5	<.5	20	.05	.205	24	12	.07	74	.012	<1	.44	.002	.03	1	<1	.4	<1	.02	3
00817	1.0	14	17	43	.8	12	4	272	3.28	11	1	<2	1	5	.7	.5	<.5	37	.06	.189	23	22	.20	77	.014	1	.86	.003	.04	1	<1	.8	<1	.02	5
00818	1.0	10	14	26	.6	8	3	279	1.73	8	<1	<2	1	5	.2	<.5	<.5	27	.06	.100	28	11	.07	64	.020	<1	.43	.002	.03	1	<1	.6	<1	.01	3
RE 00818	1.0	9	13	24	.5	8	2	253	1.64	7	<1	<2	1	5	.2	.7	<.5	26	.05	.093	27	9	.06	60	.020	<1	.38	.001	.03	1	<1	.6	<1	.01	3
00883	2.1	19	16	47	.3	14	3	189	3.86	9	1	<2	5	6	.5	.8	<.5	37	.02	.064	23	26	.26	106	.013	<1	1.17	.001	.03	1	<1	1.6	<1	.02	5
00884	2.6	23	19	54	.5	18	3	167	5.51	11	1	<2	7	6	.5	.8	<.5	55	.02	.099	22	29	.25	103	.025	<1	.96	.001	.04	1	<1	1.4	1	.02	6
00885	1.6	20	13	50	.3	18	5	177	2.53	8	1	<2	3	5	.3	<.5	<.5	30	.02	.089	30	13	.12	79	.005	1	.65	.002	.04	1	<1	.8	<1	.01	4
00886	2.1	21	16	57	.6	17	3	136	4.29	9	1	<2	5	7	.5	1.0	<.5	35	.03	.078	22	26	.31	141	.013	<1	1.01	.002	.05	1	<1	1.4	<1	.02	4
00887	1.7	12	10	34	.2	10	2	69	2.05	3	<1	<2	6	6	<.2	.6	<.5	29	.03	.026	27	13	.11	115	.018	<1	.58	.002	.03	1	<1	1.1	<1	<.01	4
00888	2.7	25	33	68	.9	19	5	335	5.48	8	1	<2	6	8	.6	.7	<.5	40	.05	.095	21	42	.24	131	.020	<1	1.24	.002	.05	1	<1	2.0	1	.02	6
00890	2.4	18	18	48	.8	15	2	123	3.66	6	1	<2	2	6	.6	1.2	<.5	28	.03	.160	18	20	.19	112	.010	<1	.72	.002	.04	1	<1	.9	<1	.03	4
00891	1.0	6	2	16	.1	5	1	39	.60	<1	<1	<2	3	4	<.2	<.5	<.5	10	.01	.015	27	4	.01	44	.005	2	.18	.001	.01	<1	<1	.4	<1	<.01	3
00892	2.5	20	14	57	.9	17	3	119	4.00	8	1	<2	3	6	.7	.8	<.5	31	.03	.043	19	24	.30	136	.011	<1	.96	.001	.05	1	<1	1.2	<1	.02	4
STANDARD C3	27.8	68	35	175	5.7	37	12	826	3.41	57	26	2	23	30	25.1	16.1	23.3	86	.61	.097	23	184	.64	164	.091	24	1.87	.043	.18	15	1	4.8	<1	.03	6
STANDARD G-2	1.4	2	3	45	<.1	7	4	561	2.03	<1	5	<2	4	77	<.2	<.5	<.5	42	.68	.103	11	83	.62	238	.135	7	.98	.094	.50	2	<1	2.8	1	<.01	5

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 3-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR DILUTED TO 10 ML. ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
- SAMPLE TYPE: SOIL SS80 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: NOV 1 2000 DATE REPORT MAILED: Nov 14/00 SIGNED BY: ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
00893	1.3	17	7	61	.2	21	6	151	2.58	8	<1	<2	9	4	.2	.5	<.5	13	.01	.028	29	11	.13	90	.004	<1	.65	.002	.04	1	<1	1.0	<1	<.01	2
00894	1.4	15	14	51	.3	16	5	261	2.86	6	1	<2	4	16	.3	.7	<.5	35	.15	.054	21	18	.28	142	.018	<1	.85	.003	.06	1	<1	1.8	<1	<.01	3
00895	1.3	6	4	12	<.1	4	1	29	.63	2	<1	<2	1	4	<.2	<.5	<.5	12	.02	.018	24	4	.02	63	.007	<1	.25	.002	.02	<1	<1	.3	<1	<.01	2
00896	1.6	13	14	39	.2	12	3	267	3.27	8	1	<2	5	8	.4	.7	<.5	22	.07	.111	22	16	.23	149	.010	<1	.81	.003	.05	1	<1	1.0	<1	<.01	3
00897	1.6	21	11	65	.7	18	7	445	2.95	7	1	<2	5	8	.2	.8	<.5	24	.04	.064	22	22	.20	158	.012	<1	1.54	.003	.06	1	<1	1.7	1	.01	3
00898	1.1	16	18	46	.2	14	4	356	2.89	9	1	<2	3	3	.2	<.5	<.5	17	.01	.092	23	10	.11	67	.005	<1	.61	.002	.04	1	<1	.8	<1	<.01	2
00900	1.0	12	13	31	.1	9	3	226	2.16	6	1	<2	2	16	<.2	<.5	<.5	21	.17	.031	24	12	.11	123	.009	<1	.73	.003	.05	1	<1	.8	<1	<.01	2
01016	1.7	8	16	24	.8	7	1	87	3.20	9	<1	<2	3	4	.4	.7	<.5	35	.02	.090	20	15	.13	88	.012	<1	.84	.002	.03	1	<1	1.0	<1	.01	3
01017	1.3	8	10	21	.6	5	2	74	1.90	6	<1	<2	6	5	<.2	<.5	<.5	23	.02	.033	23	12	.08	60	.008	<1	.84	.002	.02	1	<1	.8	<1	<.01	3
01018	1.4	7	7	19	.5	5	1	65	1.70	7	<1	<2	5	4	<.2	<.5	<.5	27	.01	.042	20	12	.10	84	.008	<1	.72	.002	.03	1	<1	.8	<1	<.01	3
01019	2.3	22	13	46	.7	14	3	194	4.29	12	1	<2	5	5	.5	.8	<.5	38	.01	.140	20	22	.23	137	.011	<1	.97	.002	.05	1	<1	1.3	<1	.01	4
01020	2.4	22	20	44	.9	14	3	102	3.99	11	1	<2	5	4	.4	1.0	<.5	25	.01	.055	20	23	.25	121	.007	<1	1.01	.002	.05	1	<1	1.2	<1	.01	3
01021	2.1	15	9	31	.4	11	3	285	2.09	11	1	<2	2	6	<.2	.8	<.5	25	.02	.049	19	12	.11	76	.010	<1	.56	.003	.03	1	<1	.7	<1	.01	3
01022	1.8	13	12	31	.3	8	2	200	4.26	7	<1	<2	6	5	.4	.8	<.5	33	.02	.077	21	19	.11	61	.016	<1	.86	.002	.03	1	<1	.8	<1	.01	4
01023	1.7	20	9	50	.3	17	4	114	2.33	10	<1	<2	5	5	.2	.7	<.5	22	.02	.058	21	17	.28	131	.010	<1	.96	.002	.04	1	<1	1.3	1	<.01	3
01024	1.7	25	10	58	.4	20	4	129	2.46	12	1	<2	6	5	<.2	<.5	<.5	21	.03	.053	20	19	.30	135	.010	<1	1.16	.002	.05	1	<1	1.5	<1	.01	3
01025	1.1	11	6	25	2.2	10	2	107	1.31	4	1	<2	3	17	<.2	<.5	<.5	13	.12	.024	23	8	.10	181	.010	<1	.37	.002	.03	1	<1	.8	<1	<.01	2
01026	1.6	9	9	26	.1	8	2	141	1.68	8	<1	<2	2	10	<.2	.6	<.5	25	.06	.030	21	9	.10	119	.014	<1	.43	.001	.03	1	<1	.6	<1	<.01	3
01027	2.0	17	22	46	.2	12	4	567	2.86	12	1	<2	4	10	.3	.7	<.5	45	.07	.204	20	15	.12	122	.032	3	.66	.002	.05	1	<1	1.2	1	.01	5
01028	1.9	10	24	27	.3	7	1	134	3.52	12	1	<2	4	6	.3	.5	<.5	39	.04	.128	19	17	.12	140	.015	<1	.70	.002	.04	1	<1	1.0	<1	.01	4
01029	1.7	16	12	34	.1	10	2	102	2.38	9	1	<2	6	8	<.2	<.5	<.5	21	.04	.030	26	11	.10	187	.010	<1	.58	.001	.03	1	<1	1.0	<1	<.01	3
01031	2.0	17	16	43	.2	12	3	139	3.69	16	1	<2	5	5	.4	.6	<.5	26	.02	.078	24	15	.15	105	.006	<1	.81	.002	.05	1	<1	1.0	1	<.01	3
01032	2.3	17	18	42	.2	12	3	144	3.69	17	1	<2	5	5	.4	1.0	<.5	26	.02	.082	24	15	.14	99	.006	<1	.79	.002	.05	1	<1	1.0	<1	<.01	3
01033	.9	8	14	36	.2	11	3	248	2.71	9	<1	<2	6	4	<.2	<.5	<.5	17	.02	.138	26	11	.12	69	.005	<1	.70	.002	.04	1	<1	.8	<1	<.01	3
01034	.8	5	14	14	.3	4	1	55	2.00	10	<1	<2	1	7	<.2	<.5	<.5	24	.05	.161	17	11	.08	71	.008	<1	.55	.003	.03	1	<1	.4	<1	.01	3
01035	.8	14	13	42	.3	14	6	473	2.55	14	1	<2	1	8	.2	<.5	<.5	22	.10	.075	22	15	.21	103	.010	<1	.91	.003	.05	1	<1	.9	<1	<.01	3
RE 01035	.7	14	13	42	.1	13	6	475	2.57	14	1	<2	1	8	.2	.6	<.5	23	.10	.075	22	15	.22	103	.010	<1	.91	.002	.05	1	<1	.8	<1	<.01	3
01036	.5	24	14	62	.2	25	9	332	3.07	18	1	<2	3	9	.3	<.5	<.5	27	.11	.087	21	22	.33	126	.011	<1	1.27	.004	.11	1	<1	1.5	<1	<.01	4
01037	.7	14	13	42	.2	14	6	365	2.28	12	1	<2	2	13	.2	.6	<.5	25	.14	.038	22	17	.22	111	.012	<1	.89	.003	.06	1	<1	1.2	<1	<.01	3
01038	.5	14	13	43	.2	15	6	377	2.36	12	1	<2	1	14	.2	<.5	<.5	25	.15	.040	21	17	.24	114	.012	<1	.94	.004	.06	1	<1	1.2	<1	<.01	3
01039	.3	15	18	49	.1	17	8	250	2.84	13	1	<2	2	9	.3	<.5	<.5	31	.08	.040	21	22	.34	112	.010	<1	1.33	.004	.07	1	<1	1.7	<1	.01	4
01040	.3	16	18	51	.1	17	8	269	2.95	14	1	<2	2	8	.3	.5	<.5	31	.08	.040	21	23	.34	110	.011	<1	1.33	.005	.06	1	<1	1.8	<1	.01	4
01041	.2	13	15	38	.1	14	5	184	2.43	11	1	<2	2	29	.3	<.5	<.5	31	.26	.029	22	19	.28	197	.012	<1	1.25	.005	.05	1	<1	1.8	<1	.01	4
01042	1.8	38	20	85	.3	34	14	483	2.98	14	2	<2	7	28	.5	1.0	<.5	24	.29	.052	23	19	.35	133	.028	<1	1.12	.005	.05	1	<1	3.0	<1	.01	4
STANDARD C3	26.1	68	33	158	5.5	33	11	762	3.10	59	26	2	21	28	25.8	17.0	22.4	77	.55	.090	20	164	.59	152	.081	21	1.91	.041	.16	15	1	4.4	<1	.02	6
STANDARD G-2	1.6	3	4	42	.1	7	3	532	1.95	<1	3	<2	5	82	<.2	<.5	<.5	41	.65	.100	10	78	.59	243	.123	1	1.16	.083	.52	2	<1	2.6	<1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01043	1.4	42	25	89	.2	38	16	682	3.44	15	2	<2	10	27	<.2	1.0	<.5	30	.36	.064	34	24	.46	132	.032	4	1.14	.007	.07	1	<1	4.1	<1	.01	5
01044	.9	36	22	79	.1	36	15	677	3.30	16	2	<2	10	70	<.2	1.2	<.5	27	1.18	.064	31	23	.48	106	.029	3	1.08	.008	.08	1	<1	4.1	<1	<.01	4
01045	.9	41	24	82	.2	45	18	800	3.73	20	2	<2	10	110	<.2	<.5	<.5	27	2.05	.069	33	28	.51	108	.028	7	1.14	.010	.09	1	<1	4.7	<1	<.01	5
01046	1.2	41	20	83	.2	48	18	775	3.62	16	2	<2	11	33	<.2	1.1	<.5	26	.52	.062	32	28	.40	117	.024	<1	1.03	.008	.07	1	<1	4.1	<1	<.01	4
01047	1.0	32	19	67	.1	38	14	596	3.09	17	2	<2	11	101	<.2	1.2	<.5	18	1.76	.068	35	22	.38	65	.026	<1	.73	.005	.04	1	<1	3.4	<1	<.01	3
01049	.6	39	24	66	.2	36	16	982	3.46	35	2	<2	12	18	<.2	1.1	<.5	17	.25	.066	37	14	.28	79	.022	<1	.68	.004	.05	2	<1	2.9	1	.01	3
01050	.6	39	28	69	.1	37	17	1177	3.65	45	2	<2	13	26	<.2	1.2	<.5	17	.36	.077	41	14	.30	94	.018	<1	.75	.006	.05	1	<1	3.2	1	.02	3
01051	.5	42	26	69	.1	37	18	933	3.70	29	2	<2	11	33	<.2	.7	<.5	26	.55	.080	38	19	.41	78	.023	5	.90	.006	.06	2	<1	3.6	<1	.02	4
01052	.5	41	27	69	.2	37	18	975	3.65	28	2	<2	11	42	<.2	<.5	<.5	24	.72	.078	38	19	.42	89	.024	<1	.93	.006	.07	1	<1	3.8	1	.01	4
01054	.3	21	30	66	.3	27	14	354	3.31	57	2	<2	9	13	<.2	.6	<.5	16	.15	.056	35	16	.25	57	.004	<1	.93	.005	.08	1	<1	2.7	<1	.01	3
01055	.4	43	40	88	.8	53	19	776	4.92	76	7	<2	7	49	.3	.7	.8	23	.75	.107	31	24	.26	107	.004	8	1.53	.010	.13	2	<1	5.1	<1	.05	5
01056	.5	18	10	33	.1	12	4	140	1.88	33	1	<2	3	26	<.2	.8	<.5	20	.33	.027	34	8	.05	48	.010	<1	.38	.003	.04	1	<1	1.1	<1	.01	3
RE 01056	.5	18	9	32	.1	11	4	138	1.84	32	1	<2	3	24	<.2	<.5	<.5	20	.32	.026	32	7	.05	46	.010	<1	.37	.006	.04	1	<1	1.0	<1	.01	3
01060	.5	14	17	49	.3	13	5	264	3.37	27	<1	<2	2	6	<.2	<.5	.6	27	.05	.108	25	17	.19	64	.010	<1	.87	.004	.07	1	<1	1.0	<1	.01	4
01061	.6	14	14	42	<.1	14	5	222	2.59	20	1	<2	2	10	<.2	.5	<.5	26	.11	.042	29	17	.23	76	.015	2	.82	.004	.06	1	<1	1.3	<1	<.01	4
01062	.6	23	20	65	.3	23	10	435	3.53	25	1	<2	2	22	<.2	.5	<.5	32	.24	.058	29	23	.29	85	.013	1	1.11	.005	.07	1	<1	1.9	<1	.01	4
01063	.5	11	18	34	.1	10	4	225	3.42	28	<1	<2	1	5	<.2	<.5	<.5	22	.04	.097	21	15	.16	49	.008	<1	.69	.003	.05	1	<1	.6	<1	.02	3
01064	.2	27	22	66	.5	22	11	571	3.45	25	2	<2	3	10	<.2	<.5	<.5	27	.11	.071	26	22	.31	93	.009	<1	1.25	.005	.08	4	<1	2.0	1	.02	4
01065	.2	34	28	88	.3	37	16	999	3.87	31	4	<2	6	16	<.2	.5	<.5	27	.19	.089	30	26	.41	128	.010	<1	1.49	.008	.09	1	<1	4.1	<1	.02	4
01066	.8	45	33	98	.3	39	16	1886	4.78	62	4	<2	4	16	<.2	.7	1.3	31	.12	.117	32	31	.31	148	.008	<1	1.88	.006	.14	2	<1	4.5	2	.03	6
01067	.9	18	17	37	<.1	15	4	164	3.30	46	1	<2	7	6	<.2	.5	.6	32	.05	.054	29	11	.06	40	.012	<1	.60	.006	.05	1	<1	1.2	1	<.01	3
01068	.7	8	15	26	<.1	8	3	111	2.62	37	<1	<2	5	4	<.2	<.5	.5	33	.03	.051	30	12	.13	47	.009	<1	.83	.003	.06	1	<1	1.0	<1	<.01	4
01069	.4	21	18	58	.5	24	8	282	3.96	18	1	<2	2	7	<.2	<.5	<.5	42	.11	.061	22	31	.45	115	.019	<1	1.40	.005	.06	1	<1	2.2	1	.01	5
01070	.2	15	13	61	.1	17	8	300	3.67	12	1	<2	5	6	<.2	<.5	<.5	47	.08	.060	23	28	.39	109	.024	2	1.44	.005	.07	2	<1	2.6	1	<.01	5
01071	.3	19	19	61	.7	23	8	187	4.38	14	1	<2	2	7	<.2	<.5	<.5	46	.13	.059	18	35	.44	115	.024	<1	1.51	.005	.06	1	<1	2.2	<1	.02	5
01072	.4	51	27	82	.2	46	18	528	4.34	18	1	<2	10	12	<.2	<.5	<.5	47	.21	.071	34	37	.63	150	.030	2	1.91	.010	.12	2	<1	6.1	<1	<.01	5
01073	.2	26	10	106	.1	44	16	667	3.53	23	1	<2	16	16	<.2	.5	<.5	12	.17	.048	39	13	.21	96	.007	3	.69	.008	.10	2	<1	2.9	<1	<.01	1
01074	.3	32	25	80	.1	27	12	523	3.68	36	2	<2	4	24	<.2	<.5	<.5	19	.34	.071	25	19	.23	102	.005	3	1.14	.006	.10	2	<1	2.3	<1	.03	3
01075	.5	34	29	82	.4	29	14	395	4.12	37	2	<2	6	28	<.2	.6	.6	23	.42	.057	29	23	.26	104	.004	3	1.38	.006	.12	2	<1	3.0	<1	.02	4
01076	.2	64	29	71	.8	36	15	967	3.80	38	8	<2	5	49	.3	.8	.7	19	.74	.096	29	23	.25	102	.005	7	1.35	.006	.12	1	<1	4.0	<1	.04	3
01077	.3	27	28	76	.1	24	10	311	4.12	36	2	<2	5	19	<.2	<.5	.5	25	.23	.039	27	20	.22	113	.006	<1	1.17	.005	.10	2	<1	1.8	1	.01	4
01078	<.2	35	24	69	.2	29	14	510	3.51	39	3	<2	8	15	<.2	<.5	<.5	19	.17	.058	38	20	.32	84	.003	<1	1.31	.005	.09	2	<1	3.5	<1	.02	3
01079	.3	21	19	51	.2	20	8	324	2.78	25	2	<2	5	29	<.2	<.5	<.5	18	.45	.046	35	17	.23	97	.004	1	1.15	.007	.10	1	<1	2.4	<1	.01	3
01080	.3	21	27	47	.2	15	7	387	3.85	34	1	<2	5	15	<.2	<.5	<.5	23	.16	.031	30	18	.16	86	.006	4	.88	.004	.07	2	<1	1.3	<1	.01	3
STANDARD G-2	1.8	3	3	45	<.1	7	3	553	2.07	<1	9	<2	5	87	<.2	<.5	<.5	42	.71	.099	11	81	.62	252	.135	<1	1.11	.091	.55	2	<1	3.1	<1	<.01	5
STANDARD C3	27.0	66	35	170	5.5	36	11	782	3.29	60	27	2	22	30	25.3	18.1	23.6	81	.59	.095	22	178	.62	162	.088	22	1.87	.044	.17	15	1	4.9	<1	.03	6

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01081	.2	30	27	62	.4	30	13	804	2.97	32	3	<2	5	52	.4	.6	<.5	18	.80	.090	30	20	.35	73	.005	4	1.14	.006	.09	2	<1	3.1	<1	.04	4
01083	.4	29	28	71	.4	33	14	866	3.52	49	3	<2	6	25	.6	.8	<.5	22	.32	.072	31	22	.33	89	.005	3	1.25	.006	.09	2	<1	3.5	<1	.03	5
01084	<.2	33	29	77	.3	32	13	687	3.66	48	3	<2	7	26	.5	.6	.5	22	.35	.060	34	20	.28	86	.005	2	1.17	.006	.10	2	<1	3.2	<1	.02	4
01085	.5	23	27	70	.2	24	11	491	3.54	50	2	<2	7	15	.6	<.5	.5	21	.14	.055	33	19	.24	86	.004	<1	1.13	.005	.10	2	<1	2.3	<1	.01	4
01086	.6	14	22	42	.3	11	4	211	3.59	27	1	<2	2	9	.5	.6	<.5	31	.11	.048	22	15	.14	79	.012	<1	.72	.003	.04	1	<1	.8	<1	.02	4
01087	.5	13	16	38	.4	12	5	248	2.67	27	1	3	2	15	<.2	.7	.5	21	.20	.058	29	12	.15	53	.007	2	.59	.003	.06	1	<1	.8	<1	<.01	3
01088	.4	11	14	33	.2	10	4	322	2.36	21	1	<2	2	16	<.2	<.5	<.5	23	.24	.047	30	14	.15	68	.009	<1	.65	.003	.06	1	<1	.9	<1	<.01	4
01089	.3	20	19	69	.5	20	9	799	2.66	27	1	<2	2	37	.2	.5	<.5	26	.54	.068	25	18	.24	102	.010	2	.93	.005	.08	1	<1	1.6	<1	.02	4
01090	<.2	23	28	83	.2	25	13	646	3.76	46	1	<2	5	11	.5	.9	<.5	26	.13	.074	26	22	.30	136	.008	3	1.19	.005	.09	1	<1	1.9	<1	.01	4
01091	.4	12	19	43	.5	12	5	215	3.59	18	<1	<2	2	5	.4	.6	<.5	35	.04	.079	22	20	.23	66	.009	<1	1.00	.003	.05	1	<1	1.0	<1	.02	5
01092	.3	12	20	25	.1	13	4	124	3.14	34	<1	<2	2	4	.3	.6	1.4	17	.02	.055	24	14	.15	39	.004	<1	.69	.002	.05	2	<1	.6	<1	.01	3
01093	.7	10	18	20	.4	6	2	157	3.20	37	<1	<2	7	4	.3	<.5	2.4	25	.02	.079	27	12	.09	40	.007	<1	.63	.002	.04	2	<1	.9	<1	<.01	4
01094	.7	30	26	62	.4	25	11	1127	4.35	40	3	<2	3	12	.5	.7	.7	33	.12	.094	27	24	.19	95	.010	<1	1.21	.004	.09	2	<1	2.2	1	.02	5
01095	.9	38	28	68	.5	29	13	1321	4.27	45	4	<2	3	16	.5	<.5	1.0	33	.16	.089	27	25	.20	106	.008	<1	1.33	.005	.11	1	<1	2.6	1	.02	5
RE 01095	.9	40	29	70	.4	30	14	1390	4.47	46	4	<2	3	17	.5	.5	1.1	34	.17	.091	27	26	.20	110	.008	1	1.38	.005	.11	2	<1	2.8	1	.02	6
01096	.7	24	27	64	.3	22	12	849	3.66	54	2	<2	5	18	.5	.6	1.9	30	.24	.069	32	18	.20	99	.007	<1	1.05	.004	.08	2	<1	2.4	<1	.01	4
01097	2.9	20	24	50	.1	18	7	297	3.87	83	1	<2	8	6	.3	.8	21.2	29	.05	.040	33	14	.13	49	.012	<1	.66	.002	.05	2	<1	1.3	1	<.01	4
01098	.7	8	17	33	.2	9	4	146	3.13	22	<1	<2	7	6	.2	<.5	1.1	37	.07	.044	30	17	.19	72	.018	<1	.93	.003	.05	2	<1	1.4	<1	<.01	5
01099	.3	16	16	50	.3	19	7	349	3.18	13	1	<2	4	6	.3	<.5	<.5	43	.10	.072	24	28	.38	90	.027	<1	1.27	.004	.06	1	<1	2.2	<1	<.01	5
01100	.2	24	15	60	.4	25	9	305	3.38	10	1	<2	4	6	.3	.6	<.5	49	.12	.057	21	38	.53	118	.030	<1	1.67	.005	.10	1	<1	2.9	<1	.01	6
01372	1.7	18	10	44	.3	13	3	164	2.39	7	<1	<2	4	6	.2	.8	<.5	33	.02	.073	23	19	.22	144	.016	1	.87	.002	.04	1	<1	1.5	<1	.01	4
01375	2.7	16	13	41	.4	13	2	109	3.71	10	1	<2	4	8	.3	1.0	<.5	51	.02	.132	21	23	.23	117	.020	<1	.77	.002	.05	1	<1	1.3	<1	.02	4
01376	1.5	11	16	24	.5	6	1	45	3.11	7	<1	<2	4	5	.2	.8	<.5	42	.01	.052	22	24	.17	115	.011	<1	1.01	.001	.03	1	<1	1.3	<1	.01	4
01377	1.6	18	21	47	.5	14	3	116	3.39	5	1	<2	6	7	.3	1.0	<.5	22	.02	.065	25	13	.09	63	.019	<1	.60	.002	.02	1	<1	1.1	<1	.01	3
01378	1.1	13	17	27	.4	7	1	62	3.68	7	1	<2	8	5	.3	1.0	<.5	33	.02	.053	26	22	.14	64	.008	<1	.93	.002	.03	1	<1	1.1	1	.01	4
01379	1.9	24	18	59	.4	19	4	138	4.43	9	1	<2	2	8	.3	1.0	<.5	26	.09	.104	19	24	.30	113	.008	1	.95	.003	.05	1	<1	1.0	<1	.02	3
01380	1.0	15	22	46	.7	11	3	123	4.36	9	1	<2	6	5	.3	<.5	<.5	31	.02	.063	23	23	.21	71	.011	<1	1.19	.002	.05	1	<1	1.3	<1	.01	4
01381	.7	15	15	35	.2	12	4	157	4.09	10	1	<2	3	5	.3	.5	<.5	38	.08	.081	22	16	.16	40	.007	1	.79	.002	.04	1	<1	.7	<1	.02	3
01382	1.0	12	12	32	.2	10	3	120	2.47	7	1	<2	2	7	<.2	<.5	<.5	29	.07	.202	23	13	.14	71	.008	<1	.61	.002	.04	1	<1	.6	<1	.01	3
01383	.9	12	16	33	.5	10	3	128	2.60	9	1	<2	3	6	.2	<.5	<.5	34	.04	.167	26	16	.17	113	.014	<1	.77	.002	.05	1	<1	1.1	<1	<.01	4
01384	1.4	16	17	48	.2	17	4	153	4.31	10	1	<2	2	6	.3	.6	<.5	33	.04	.093	22	28	.24	90	.009	<1	.93	.002	.05	1	<1	1.0	<1	.02	4
01385	1.6	13	16	45	.3	13	3	155	4.01	8	1	<2	6	7	.3	.7	<.5	33	.06	.086	27	21	.22	102	.010	<1	.90	.002	.05	1	<1	1.1	<1	<.01	3
01386	1.2	12	13	32	.1	9	2	182	2.19	4	1	<2	2	15	<.2	<.5	<.5	32	.28	.041	29	11	.10	150	.013	<1	.59	.002	.04	1	<1	1.0	<1	<.01	3
01387	1.1	27	25	70	.6	22	12	2325	2.96	6	4	<2	1	37	.5	<.5	<.5	31	.67	.106	19	20	.21	241	.010	<1	1.27	.005	.07	1	<1	1.5	<1	.03	4
STANDARD C3	27.0	69	36	168	5.6	36	11	804	3.33	58	26	2	22	30	23.9	16.0	23.0	84	.60	.094	23	183	.63	159	.090	23	1.81	.042	.17	15	1	4.6	<1	.02	6
STANDARD G-2	1.7	3	3	45	<.1	7	4	565	2.05	<1	3	<2	5	76	<.2	<.5	<.5	43	.68	.104	12	86	.63	238	.135	5	.95	.085	.49	3	<1	2.8	<1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01388	1.1	42	23	77	1.2	36	16	1203	3.39	7	6	<2	2	44	.5	.7	<.5	26	.79	.097	24	23	.28	237	.012	4	1.41	.006	.08	1	<1	2.4	<1	.03	3
01389	.8	30	22	55	.3	21	5	198	2.83	6	3	<2	3	17	.2	<.5	<.5	25	.17	.064	24	17	.13	168	.010	<1	.88	.003	.06	1	<1	1.9	<1	.02	3
01390	.7	26	13	47	.2	33	7	238	3.14	7	1	<2	2	17	.2	.5	<.5	28	.21	.051	25	19	.12	142	.012	<1	.66	.003	.04	1	<1	1.5	<1	<.01	3
01391	.8	29	11	61	.2	65	15	450	4.17	7	1	<2	3	26	.4	.6	<.5	48	.35	.065	24	75	.28	135	.018	<1	.92	.003	.04	1	<1	2.6	<1	.01	5
01392	.5	44	19	64	.4	79	23	1382	3.57	11	2	<2	3	30	.5	<.5	<.5	43	.43	.105	26	125	.42	168	.017	1	1.45	.004	.06	1	<1	6.1	<1	.02	4
01393	.3	26	15	81	.3	37	13	850	3.07	12	2	<2	3	21	.3	.5	<.5	20	.32	.070	22	28	.35	123	.010	1	1.00	.003	.05	1	<1	2.2	<1	.02	2
01395	.8	19	10	52	.2	38	14	1300	2.78	15	1	<2	3	16	.2	<.5	<.5	25	.19	.078	21	42	.23	172	.007	<1	1.00	.003	.05	1	<1	2.1	<1	.01	3
01396	1.3	22	23	42	.4	25	10	984	3.32	17	2	<2	1	40	.3	.7	<.5	27	.28	.094	22	17	.07	186	.007	<1	.94	.005	.04	1	<1	1.2	1	.03	4
01397	2.3	21	20	42	.1	16	3	113	2.68	29	<1	<2	7	10	<.2	.8	<.5	29	.04	.055	29	12	.06	101	.005	<1	.53	.002	.04	1	<1	1.0	1	.02	4
01398	1.7	20	26	40	.1	14	3	115	2.80	13	1	<2	4	8	<.2	.7	<.5	32	.02	.102	25	11	.04	79	.007	1	.51	.002	.04	1	<1	.9	<1	.02	3
01399	1.5	24	20	43	.2	16	4	207	4.32	9	1	<2	6	8	.3	<.5	<.5	26	.02	.169	23	19	.13	104	.011	<1	.76	.003	.05	1	<1	1.1	1	.02	4
01400	.5	9	13	26	.4	10	3	229	2.42	12	<1	<2	1	5	<.2	<.5	<.5	22	.05	.116	22	16	.17	68	.006	<1	.74	.002	.05	1	<1	.5	<1	.01	3
01601	.7	15	17	43	.4	17	7	1050	2.12	4	5	<2	2	62	<.2	<.5	<.5	10	.86	.127	13	12	.21	150	.005	1	.65	.005	.04	1	<1	1.3	<1	.06	1
01602	.4	13	24	45	.2	16	12	381	2.16	3	3	<2	4	28	.2	<.5	<.5	8	.30	.071	20	8	.13	116	.002	<1	.61	.003	.03	1	<1	1.2	<1	.03	1
01603	.5	19	16	48	.5	21	9	761	2.56	7	5	<2	3	24	.2	<.5	<.5	15	.32	.079	22	16	.22	151	.007	<1	1.07	.003	.06	1	<1	2.3	<1	.02	2
01604	1.0	35	27	64	.6	25	17	1123	3.45	10	3	<2	2	24	.5	.5	<.5	29	.30	.058	26	21	.20	176	.011	1	1.18	.004	.07	1	<1	1.8	<1	.01	4
01605	.9	36	33	48	2.7	38	19	655	3.50	7	7	<2	3	45	.7	<.5	<.5	22	.70	.168	21	27	.22	178	.009	<1	1.97	.005	.08	1	1	2.7	<1	.05	4
01608	.4	44	21	67	.7	64	21	1556	3.49	9	3	<2	3	27	.4	.6	<.5	16	.49	.058	20	27	.33	145	.009	1	.88	.005	.05	1	<1	4.0	<1	.02	2
01611	<.2	51	30	87	.5	47	22	965	4.46	34	1	<2	13	22	.5	<.5	.5	31	.29	.074	42	26	.57	99	.020	1	1.34	.006	.09	2	<1	4.5	<1	<.01	5
01612	.3	45	29	81	.2	41	20	899	4.00	33	1	<2	13	44	.5	<.5	<.5	30	.72	.070	41	24	.55	96	.022	1	1.26	.006	.08	1	<1	4.2	<1	<.01	4
01613	1.1	50	18	124	.2	54	14	364	5.01	36	3	<2	13	23	.4	.7	<.5	12	.16	.072	29	14	.16	78	.006	<1	.75	.005	.05	1	<1	3.3	<1	.02	3
01614	.3	40	25	80	.2	39	18	737	3.63	28	2	<2	11	72	.5	<.5	.5	29	1.23	.075	35	22	.51	92	.028	1	1.13	.006	.07	1	<1	3.8	<1	<.01	4
01615	.7	41	24	92	.2	44	20	605	3.74	21	2	<2	11	40	.5	.5	<.5	27	.56	.077	30	23	.49	98	.030	1	1.20	.006	.08	1	<1	3.5	<1	.01	4
RE 01615	.4	42	25	92	.2	43	20	607	3.78	21	3	<2	11	41	.5	<.5	<.5	27	.57	.077	30	23	.49	98	.030	<1	1.21	.005	.08	1	<1	3.5	<1	.01	4
01616	.6	40	25	88	.2	42	20	652	3.74	22	2	<2	11	24	.5	.7	<.5	25	.31	.077	31	21	.46	82	.026	<1	1.08	.005	.06	1	<1	3.2	<1	.01	4
01617	14.2	95	47	270	.4	460	119	8379	13.20	156	6	<2	10	29	2.7	<.5	.5	26	.65	.216	93	26	.20	603	.002	<1	.35	.002	.02	3	<1	20.3	1	<.01	1
01619	.5	44	25	73	.2	38	18	942	3.52	34	1	<2	12	113	.6	.5	1.3	26	2.08	.074	34	19	.46	98	.026	<1	.97	.006	.08	1	<1	3.9	<1	<.01	4
01620	.3	42	25	72	.2	37	17	830	3.45	37	2	<2	13	77	.4	<.5	<.5	24	1.40	.073	39	17	.42	85	.023	2	.88	.006	.07	2	<1	3.4	<1	<.01	3
01621	.6	44	25	79	.3	42	20	1160	3.55	46	2	<2	13	48	.5	.9	.7	22	.84	.071	38	17	.38	106	.019	<1	.89	.005	.07	1	<1	3.3	<1	<.01	3
01651	.4	13	12	25	.4	7	2	100	2.20	12	<1	<2	1	6	<.2	<.5	<.5	28	.06	.069	23	13	.12	89	.009	<1	.60	.002	.04	1	<1	.6	<1	.01	4
01652	.6	79	29	86	.9	59	24	1829	4.53	22	5	<2	4	22	.6	<.5	.5	46	.30	.122	40	47	.48	270	.010	1	2.17	.007	.16	2	<1	6.5	<1	.03	7
01653	.6	37	18	60	.3	38	13	536	3.31	15	2	<2	3	18	.5	.6	<.5	32	.23	.068	33	30	.32	125	.008	<1	1.17	.004	.09	3	<1	3.4	<1	.02	4
01654	.3	38	26	65	.1	36	15	711	3.20	21	1	<2	6	15	.4	<.5	<.5	28	.22	.053	34	23	.40	103	.016	<1	1.12	.004	.09	1	<1	3.7	<1	.01	4
01655	.7	32	15	60	.6	33	10	707	2.62	15	2	<2	2	31	.4	.9	<.5	21	.43	.080	23	20	.23	111	.007	<1	.91	.004	.05	1	<1	2.3	<1	.04	3
STANDARD C3	26.4	70	36	168	5.5	35	11	800	3.30	61	26	3	22	30	25.2	15.8	22.8	84	.60	.094	22	181	.63	159	.092	28	1.83	.044	.17	15	1	4.8	<1	.02	6
STANDARD G-2	1.3	3	3	44	<.1	7	4	551	1.99	<1	3	<2	4	74	<.2	<.5	<.5	41	.67	.102	11	82	.61	233	.131	<1	.93	.084	.48	3	<1	2.7	<1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data / FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01656	.3	22	18	53	.4	21	11	453	2.95	13	2	<2	2	12	.4	.5	<.5	27	.25	.077	21	27	.28	64	.012	2	1.08	.005	.05	1	<1	2.0	<1	.02	4
01657	.4	31	17	57	.2	30	9	348	2.83	15	1	<2	2	19	.5	.9	<.5	31	.38	.094	25	22	.22	121	.009	4	1.08	.005	.07	1	<1	2.1	<1	.02	5
01658	2.9	88	14	202	.2	123	33	1297	4.85	45	2	<2	6	20	1.4	6.1	<.5	35	.39	.163	26	36	.51	63	.009	4	1.17	.003	.04	1	<1	5.7	<1	<.01	5
01659	1.0	57	15	109	.2	71	24	584	4.08	21	2	<2	7	29	.9	2.2	<.5	37	.41	.111	27	36	.43	71	.021	5	1.13	.008	.06	1	<1	5.5	<1	<.01	5
01660	.8	62	9	103	.2	84	29	763	4.59	17	2	<2	6	31	.9	3.3	<.5	66	.40	.135	24	87	.74	62	.056	<1	1.34	.011	.04	1	<1	7.3	<1	<.01	6
01661	.7	60	23	118	.4	75	29	1114	4.74	34	2	<2	9	31	.9	.6	<.5	46	.36	.089	28	50	.62	121	.036	4	1.53	.012	.10	2	<1	6.2	<1	<.01	6
01792	<.2	29	22	62	.5	30	12	500	3.10	34	2	<2	5	26	.6	.5	<.5	18	.44	.062	28	19	.31	68	.004	<1	1.16	.005	.08	1	<1	2.2	<1	.02	4
01793	.2	50	25	52	.3	26	13	373	3.31	31	3	<2	5	27	.7	.6	<.5	24	.43	.055	33	20	.22	75	.005	2	1.15	.005	.08	1	<1	2.8	<1	.02	4
01794	<.2	58	27	76	.5	39	18	867	3.78	47	4	<2	8	37	.6	<.5	<.5	20	.60	.065	38	23	.40	64	.003	2	1.23	.006	.09	2	<1	3.9	<1	.03	4
01795	<.2	30	28	61	.3	20	10	446	3.85	41	1	<2	4	17	.5	<.5	<.5	30	.27	.044	30	17	.25	76	.006	<1	1.02	.006	.07	2	<1	1.6	<1	.01	5
01796	.5	31	33	65	.2	24	11	501	4.30	46	1	<2	5	19	.5	<.5	<.5	30	.33	.047	33	23	.28	90	.005	<1	1.21	.006	.09	2	<1	1.6	<1	.01	5
01797	<.2	40	26	72	.4	36	15	755	3.52	39	2	<2	7	24	.6	<.5	<.5	21	.39	.055	33	22	.32	86	.003	<1	1.28	.006	.11	2	<1	3.0	<1	.02	4
01798	<.2	35	25	68	.2	32	14	591	3.37	36	2	<2	7	20	.7	.5	<.5	20	.24	.065	34	21	.31	92	.003	<1	1.33	.006	.10	2	<1	3.0	<1	.02	4
01800	<.2	32	26	73	.2	36	15	809	3.36	41	3	<2	7	49	.5	<.5	<.5	17	.77	.065	29	21	.36	61	.004	3	1.16	.006	.09	1	<1	3.2	<1	.03	3
RE 01800	<.2	32	26	74	.2	35	15	821	3.40	42	3	<2	7	50	.6	<.5	<.5	16	.79	.066	29	21	.36	61	.003	4	1.17	.007	.09	1	<1	3.2	<1	.03	3
01822	.7	26	23	68	.3	25	7	310	3.33	40	1	<2	3	8	.5	1.6	1.2	19	.04	.056	23	18	.19	45	.007	<1	.71	.004	.04	2	<1	1.1	1	.02	3
01823	.9	31	29	114	.7	34	15	1098	3.53	36	2	<2	2	22	.7	.9	.6	22	.19	.080	21	20	.23	110	.006	1	.91	.005	.06	1	<1	2.1	<1	.02	3
01824	.9	31	21	89	.6	30	8	399	2.99	31	1	<2	2	22	.5	.8	1.7	23	.22	.076	22	17	.19	158	.006	<1	.82	.004	.06	1	<1	1.5	<1	.02	3
01827	1.5	35	21	88	.5	29	10	649	3.01	31	2	<2	2	31	.6	.8	<.5	20	.21	.079	20	15	.16	109	.005	<1	.70	.004	.05	1	<1	1.6	<1	.02	2
01828	1.3	19	19	66	.2	23	9	404	3.18	33	1	<2	2	17	.5	.8	1.0	26	.15	.056	24	25	.21	90	.007	<1	.75	.004	.04	1	<1	1.3	<1	.01	3
01829	1.5	29	17	64	.3	25	10	584	2.58	26	1	<2	1	26	.4	.7	1.0	27	.15	.071	24	21	.16	137	.007	<1	.76	.005	.06	1	<1	1.3	<1	.02	3
01830	.9	11	11	23	.2	8	2	227	2.03	18	<1	<2	2	12	.2	<.5	.8	21	.04	.090	25	15	.09	56	.008	1	.52	.004	.03	1	<1	.6	1	<.01	3
01831	1.7	22	21	53	.4	21	5	378	3.76	42	1	<2	2	23	.7	1.0	.6	44	.06	.221	20	24	.16	79	.011	<1	.65	.005	.04	1	<1	1.1	<1	.02	4
01832	1.0	15	11	36	.6	15	3	194	2.48	21	1	<2	1	12	.4	<.5	<.5	24	.06	.076	23	17	.11	97	.008	<1	.64	.003	.04	1	<1	.7	<1	.01	3
01833	.9	23	11	90	.8	28	11	556	4.05	27	2	<2	1	26	.7	.9	<.5	32	.33	.108	20	23	.19	75	.011	<1	.88	.004	.04	1	<1	1.3	<1	.02	4
01834	.9	24	13	94	.9	30	12	567	4.07	28	2	<2	1	25	.7	.9	<.5	30	.31	.107	19	25	.20	72	.010	<1	.95	.004	.04	1	<1	1.4	<1	.02	4
01835	1.0	34	13	56	.3	21	5	285	3.01	20	1	<2	1	14	.5	.9	<.5	30	.12	.156	24	18	.07	100	.014	<1	.52	.003	.04	1	<1	.9	<1	.01	3
01836	1.2	24	12	56	.2	27	6	135	3.22	38	1	<2	1	12	.7	1.2	.6	24	.13	.051	22	17	.12	65	.007	<1	.58	.003	.03	1	<1	.7	<1	.01	3
01837	.8	25	12	48	.2	20	5	143	2.96	24	1	<2	2	12	.5	1.2	.5	26	.12	.045	25	15	.08	59	.011	<1	.55	.003	.03	1	<1	.9	<1	.01	3
01838	.8	28	13	63	.3	33	7	407	3.06	21	1	<2	3	13	.6	.5	.6	28	.15	.056	25	15	.11	59	.015	<1	.61	.004	.03	1	<1	1.4	<1	.02	3
01839	1.2	36	12	137	.4	70	19	806	6.36	27	2	3	4	13	.7	.5	.5	26	.12	.064	24	24	.24	74	.011	<1	1.12	.004	.06	2	<1	2.2	1	.01	4
01840	1.0	24	11	81	.5	29	9	670	3.84	23	1	<2	2	10	.7	.8	<.5	21	.04	.117	23	17	.14	74	.009	1	.71	.004	.04	1	<1	.8	1	.01	2
01841	.9	22	10	79	.5	30	9	709	3.81	22	1	<2	2	10	.6	.5	<.5	22	.04	.126	22	16	.13	69	.009	<1	.66	.004	.04	1	<1	.7	1	.02	2
01842	.7	11	14	31	.5	11	3	145	2.81	18	1	<2	2	5	.4	.5	<.5	24	.04	.076	21	15	.12	48	.013	<1	.70	.003	.03	1	<1	.7	<1	.02	2
STANDARD C3	26.7	68	35	166	5.5	35	11	798	3.21	61	25	<2	23	30	25.2	16.8	22.3	83	.59	.094	22	176	.62	159	.086	23	1.86	.044	.17	15	2	4.7	<1	.02	6
STANDARD G-2	1.6	3	4	45	<.1	7	4	559	2.03	<1	4	<2	5	82	<.2	<.5	<.5	44	.69	.103	11	82	.62	248	.133	1	1.09	.124	.53	2	1	2.8	<1	<.01	5

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01843	.9	11	21	28	.3	11	2	94	3.44	29	<1	<2	5	5	<.2	.5	1.7	45	.04	.128	23	20	.13	52	.017	3	.76	.003	.04	1	<1	1.2	<1	.01	3
01844	.7	13	16	33	.1	12	3	107	2.96	22	<1	<2	5	5	<.2	.7	1.4	30	.04	.074	26	19	.14	52	.012	<1	.76	.003	.04	1	<1	1.1	<1	<.01	3
01845	.9	37	17	71	.1	35	14	484	3.55	27	1	<2	8	10	<.2	1.2	1.3	24	.09	.067	28	19	.27	59	.023	1	.73	.003	.05	1	<1	2.3	<1	<.01	2
01846	1.2	10	11	26	.2	10	2	78	1.69	6	<1	<2	1	5	<.2	<.5	<.5	18	.04	.065	25	7	.04	55	.005	3	.38	.002	.03	1	<1	.2	<1	.01	2
01847	2.1	27	9	51	.8	19	4	150	1.73	8	1	<2	3	12	<.2	.9	<.5	18	.04	.055	19	14	.21	147	.010	<1	.55	.002	.05	1	<1	1.1	<1	.02	2
01848	3.1	37	12	68	.6	25	6	194	2.27	13	2	<2	4	10	<.2	1.3	<.5	18	.03	.051	21	14	.16	95	.009	<1	.60	.002	.05	1	<1	1.4	<1	.02	2
01849	3.2	37	12	69	.5	26	6	209	2.31	13	2	<2	3	11	<.2	1.2	<.5	18	.03	.055	19	15	.16	92	.010	<1	.58	.002	.05	1	<1	1.4	1	.02	2
01850	1.6	31	14	66	.8	26	5	151	2.78	11	1	<2	4	12	<.2	.6	<.5	25	.04	.053	21	23	.33	210	.014	4	.94	.002	.07	1	<1	1.7	1	.02	3
01851	1.6	30	14	64	.9	25	5	146	2.59	11	1	<2	3	11	<.2	<.5	<.5	26	.04	.053	20	22	.31	218	.013	<1	.93	.002	.07	1	<1	1.5	<1	.02	3
01852	1.5	21	19	53	.9	19	4	117	3.99	29	1	<2	1	9	<.2	.5	.9	30	.04	.118	15	18	.13	81	.007	1	.66	.002	.04	2	<1	.8	<1	.03	3
01853	1.0	7	12	15	.3	6	1	50	1.93	23	<1	<2	1	6	<.2	<.5	.9	21	.01	.133	17	10	.06	44	.004	<1	.43	.002	.02	1	<1	.2	<1	.02	2
01854	1.0	7	12	16	.4	7	1	42	1.94	27	<1	<2	1	5	<.2	<.5	1.0	18	.01	.142	16	10	.06	41	.004	<1	.42	.002	.02	1	<1	.2	<1	.02	2
01856	1.4	9	24	20	1.0	6	1	33	2.84	28	<1	<2	5	8	<.2	<.5	1.3	45	.02	.064	20	14	.06	65	.009	2	.52	.001	.03	1	<1	.8	<1	.01	4
01857	1.9	41	32	95	1.4	33	6	157	4.16	41	1	<2	4	12	<.2	.8	.8	19	.01	.081	20	19	.17	92	.004	3	.75	.002	.05	1	<1	1.4	<1	.02	3
01858	.8	6	9	9	.7	3	<1	13	1.19	11	<1	<2	3	5	<.2	<.5	.6	14	.02	.030	20	6	.01	49	.003	<1	.37	.001	.02	1	<1	.4	1	.01	2
01859	1.3	49	25	116	2.2	45	13	424	3.81	35	1	<2	3	16	.2	.9	1.2	19	.06	.076	23	19	.21	76	.010	7	.74	.002	.04	2	<1	2.2	<1	.02	2
01861	.9	7	9	16	.3	5	1	30	1.16	9	<1	<2	2	7	<.2	<.5	.6	17	.04	.120	21	6	.02	33	.004	<1	.32	.002	.02	1	<1	.5	<1	.01	4
01862	2.2	20	28	51	.7	15	2	100	5.28	34	1	<2	2	13	<.2	.9	1.2	50	.06	.385	15	20	.11	62	.007	2	.65	.002	.03	1	<1	.8	<1	.03	5
01863	1.8	17	25	42	.6	12	2	73	4.50	35	1	<2	1	12	<.2	.8	1.4	54	.05	.364	15	17	.08	55	.006	1	.59	.002	.03	1	<1	.6	<1	.03	4
01864	1.0	5	18	10	1.2	4	<1	27	2.04	29	<1	<2	1	11	<.2	<.5	1.0	36	.03	.144	19	10	.04	40	.008	<1	.49	.002	.02	1	<1	.4	<1	.02	3
01865	2.4	32	15	49	.5	21	4	164	3.74	53	1	<2	2	30	<.2	1.0	1.6	26	.05	.247	19	13	.08	70	.006	2	.45	.002	.04	1	<1	1.0	<1	.04	3
RE 01865	2.3	31	15	49	.6	21	4	158	3.52	53	1	<2	2	30	<.2	1.0	1.3	26	.05	.243	18	14	.08	69	.006	2	.44	.002	.04	1	<1	.9	<1	.04	3
01866	2.5	24	13	36	.3	14	3	82	1.69	26	<1	<2	2	13	.2	1.0	1.2	19	.02	.078	26	5	.02	45	.003	4	.28	.001	.02	1	<1	.5	<1	.01	3
01867	.7	7	6	13	.3	5	1	34	.58	14	<1	<2	2	9	<.2	<.5	.7	7	.04	.028	24	6	.02	34	.003	<1	.24	.001	.02	2	<1	.5	<1	<.01	3
01868	.6	5	7	12	.2	4	1	34	.55	14	<1	<2	2	9	<.2	<.5	.7	7	.03	.029	23	4	.02	31	.003	3	.25	.001	.02	3	<1	.4	<1	<.01	3
01869	2.4	38	14	61	.4	27	6	146	6.30	171	3	<2	2	48	.4	.9	1.6	54	.15	.451	16	32	.29	84	.024	7	.98	.003	.04	2	<1	1.9	<1	.03	4
01870	1.6	15	21	38	.2	14	3	115	3.35	36	1	<2	3	12	<.2	.8	1.5	26	.03	.050	19	16	.10	63	.010	<1	.50	.001	.02	2	<1	1.1	<1	.02	3
01871	1.2	29	15	52	.4	21	4	85	2.52	14	1	<2	<1	19	.2	.7	<.5	22	.08	.047	19	16	.10	92	.006	<1	.62	.002	.04	1	<1	.6	<1	.02	3
01872	.9	8	10	14	.4	5	<1	33	1.42	6	<1	<2	1	6	<.2	<.5	<.5	26	.05	.042	17	9	.03	104	.004	<1	.44	.001	.03	1	<1	.4	<1	.02	3
01874	1.7	21	19	55	.2	22	5	162	4.33	29	1	<2	4	10	<.2	.7	1.0	32	.07	.083	21	21	.19	124	.015	<1	.72	.002	.05	1	<1	1.3	1	.02	4
01875	1.1	8	17	22	.2	8	1	54	2.60	13	1	<2	4	9	<.2	<.5	<.5	31	.05	.105	19	13	.08	96	.007	<1	.53	.001	.03	1	<1	.8	<1	.02	3
01876	1.4	11	14	22	.2	10	1	54	2.62	32	<1	<2	1	13	<.2	.8	1.5	31	.04	.124	19	15	.07	46	.008	<1	.47	.002	.03	1	<1	.5	<1	.02	3
01877	1.2	13	12	28	.3	11	2	74	2.21	18	1	<2	1	12	<.2	.5	.5	25	.05	.069	18	15	.08	72	.008	<1	.57	.002	.03	1	<1	.6	<1	.02	3
01878	1.3	8	9	15	.4	5	1	30	1.74	11	1	<2	<1	10	<.2	<.5	<.5	20	.07	.076	16	11	.04	65	.007	<1	.43	.001	.03	1	<1	.5	<1	.02	2
STANDARD C3	28.1	70	37	172	5.7	36	12	824	3.55	59	25	3	23	30	24.7	17.9	24.1	86	.60	.097	22	178	.65	162	.087	22	1.84	.043	.17	15	1	5.1	<1	.03	6
STANDARD G-2	1.5	3	3	45	<.1	7	4	544	2.05	<1	3	<2	4	76	<.2	<.5	<.5	41	.66	.101	11	80	.62	244	.130	3	.94	.104	.52	2	<1	2.9	<1	<.01	4

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data___ FA ____

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
01879	1.5	43	22	76	.2	34	13	598	3.70	14	2	<2	6	12	.2	1.7	<.5	15	.08	.060	26	14	.20	87	.008	6	.65	.004	.05	1	<1	2.1	1	.02	2
01880	2.2	22	17	49	.8	15	5	751	2.38	12	1	<2	2	15	.3	.8	<.5	21	.04	.082	23	15	.15	78	.010	1	.59	.002	.04	1	<1	1.0	<1	.02	2
01881	3.6	34	14	74	.3	24	5	213	2.96	15	1	<2	3	12	.2	1.3	<.5	27	.05	.097	20	17	.22	106	.010	<1	.69	.003	.06	1	<1	1.2	<1	.02	2
01882	3.8	42	15	83	.5	28	9	552	3.24	16	2	<2	3	14	<.2	1.7	<.5	23	.05	.102	21	21	.26	135	.011	5	.92	.002	.06	1	<1	1.5	1	.02	2
01932	1.2	27	14	65	.2	25	7	223	3.96	10	1	<2	7	6	<.2	.5	<.5	19	.03	.050	23	21	.22	50	.006	4	.91	.001	.04	1	<1	1.5	<1	.02	2
01933	1.4	30	15	73	.1	28	8	231	3.79	11	1	<2	7	6	<.2	.5	<.5	15	.02	.046	22	22	.24	56	.006	<1	1.03	.002	.04	1	<1	1.5	1	.02	2
01934	1.3	26	14	62	.3	24	6	226	4.00	10	1	<2	7	5	<.2	.5	<.5	15	.03	.052	20	19	.21	47	.005	<1	.83	.002	.04	1	<1	1.3	2	.02	2
01935	1.3	25	14	59	.3	23	6	220	4.01	10	1	<2	6	5	<.2	.9	<.5	19	.03	.048	20	18	.20	46	.005	4	.79	.002	.04	1	<1	1.2	1	.02	2
01936	1.7	12	15	33	.2	10	2	84	3.03	7	1	<2	6	5	<.2	.7	<.5	27	.02	.120	26	12	.10	44	.015	1	.58	.001	.02	1	<1	1.0	<1	.01	3
01937	.9	23	17	61	.3	22	6	176	3.46	8	1	<2	6	6	<.2	<.5	<.5	13	.01	.048	21	15	.22	61	.003	5	.85	.004	.05	1	<1	1.2	<1	.02	1
01938	1.5	16	15	37	.4	12	3	118	3.35	10	1	<2	3	6	<.2	<.5	<.5	20	.02	.158	20	15	.13	53	.007	<1	.72	.002	.03	1	<1	.9	1	.02	2
01939	1.8	14	11	28	.5	12	1	47	2.66	13	1	<2	2	6	.2	<.5	<.5	35	.01	.079	17	15	.12	68	.004	7	.66	.001	.03	1	<1	.6	<1	.02	3
01940	2.3	23	16	57	1.0	22	4	109	4.32	12	1	<2	4	6	<.2	1.0	<.5	29	.01	.076	17	30	.30	155	.007	<1	1.15	.002	.04	1	<1	1.3	<1	.02	2
01941	1.8	20	18	50	.2	18	4	148	5.41	13	1	<2	6	7	<.2	.9	<.5	27	.03	.171	24	25	.21	73	.010	<1	.89	.002	.04	1	<1	1.2	<1	.01	3
01942	1.8	20	17	52	.2	17	4	146	5.21	13	1	<2	7	7	<.2	<.5	<.5	27	.02	.103	25	25	.21	59	.009	<1	.94	.002	.04	1	<1	1.3	<1	.01	3
01943	.8	15	14	39	.3	13	3	101	2.72	12	1	<2	7	11	<.2	.6	<.5	24	.02	.069	27	12	.11	61	.004	2	.72	.003	.04	1	<1	1.0	1	.01	2
01945	1.0	10	10	20	.2	6	1	66	2.05	16	<1	<2	2	19	.2	.6	<.5	25	.04	.153	22	9	.04	63	.005	1	.31	.002	.03	1	<1	.4	<1	.02	2
RE 01945	1.1	10	11	20	.3	6	1	66	2.06	17	<1	<2	3	19	.2	<.5	<.5	26	.04	.153	23	9	.04	64	.005	1	.31	.002	.03	1	<1	.4	<1	.02	2
01946	.4	2	2	6	.3	2	<1	8	.25	3	<1	<2	4	5	<.2	<.5	<.5	12	.02	.014	27	4	.02	52	.002	5	.39	.001	.01	<1	<1	.4	<1	<.01	3
01947	2.0	19	18	54	.1	16	3	92	4.78	11	1	<2	5	9	<.2	1.1	<.5	43	.04	.148	20	32	.24	145	.013	<1	1.24	.002	.05	1	<1	1.8	1	.02	4
01948	2.5	24	15	58	.3	20	4	103	3.72	14	1	<2	5	10	<.2	1.0	<.5	45	.03	.141	22	24	.24	205	.011	4	.85	.004	.05	1	<1	1.3	1	.02	2
01949	2.6	25	24	54	.6	16	3	96	5.57	24	1	<2	4	13	<.2	1.7	<.5	42	.02	.183	20	22	.17	117	.010	<1	.81	.004	.03	1	<1	1.2	1	.02	3
01950	2.7	27	39	73	1.4	23	4	117	6.73	20	1	<2	2	11	.3	.9	.8	55	.04	.378	14	24	.13	108	.008	<1	.77	.002	.03	1	<1	1.0	1	.03	4
01951	.4	3	<2	5	.1	1	<1	31	.15	<1	<1	<2	4	2	<.2	<.5	<.5	6	.03	.012	30	3	.02	34	.004	1	.22	.001	.01	<1	<1	.3	<1	<.01	3
01952	1.3	15	35	31	1.4	8	1	56	3.87	48	1	<2	2	8	<.2	1.2	.6	42	.02	.126	19	14	.06	54	.008	6	.66	.002	.03	1	<1	.4	<1	.03	1
01953	.5	4	<2	7	.6	2	1	18	.30	2	<1	<2	3	2	.2	<.5	<.5	6	.03	.014	28	3	.01	34	.005	<1	.21	.001	.01	<1	<1	.3	<1	<.01	3
01961	.9	12	18	25	.4	7	1	100	3.07	23	<1	<2	3	4	<.2	.9	.5	22	.02	.121	18	14	.10	39	.004	<1	.72	.001	.02	2	<1	.6	<1	.02	1
01962	1.3	23	20	62	.3	18	5	214	4.69	36	1	<2	4	4	<.2	.5	1.3	15	.01	.096	20	23	.19	52	.004	<1	1.04	.002	.03	5	<1	.9	1	.02	2
351561	.9	45	38	75	.2	42	19	860	3.71	49	2	<2	11	71	.2	.6	.7	14	1.48	.061	27	17	.37	83	.007	5	.92	.009	.14	1	<1	3.4	<1	.03	1
351562	.6	41	38	73	.3	41	17	830	3.66	40	2	<2	11	19	.2	.5	<.5	17	.25	.071	39	19	.32	84	.007	5	.91	.005	.09	1	<1	3.3	<1	.01	1
351563	.8	52	51	84	.3	51	21	1009	4.15	48	2	<2	13	38	.2	.6	.9	17	.81	.071	36	18	.32	82	.007	<1	.90	.006	.10	1	<1	3.7	<1	<.01	1
351565	.5	36	30	73	.5	37	16	674	4.14	35	2	<2	5	15	<.2	<.5	.9	24	.22	.076	26	30	.38	134	.006	4	1.49	.006	.11	1	<1	3.4	<1	.02	2
351566	.3	34	27	67	.5	38	15	683	3.46	28	2	<2	4	16	.2	<.5	.6	30	.26	.076	27	27	.37	105	.006	<1	1.26	.005	.09	2	<1	3.6	<1	.02	2
351567	.3	26	26	60	.4	28	13	506	3.36	29	2	<2	3	16	.2	.5	.7	30	.23	.061	27	25	.34	93	.006	<1	1.18	.004	.09	1	<1	2.7	<1	.02	2
STANDARD G-2	1.6	3	3	47	<.1	7	4	570	2.11	<1	4	<2	4	75	.2	<.5	<.5	40	.68	.104	10	80	.64	242	.135	1	.98	.091	.51	2	<1	3.0	<1	<.01	4
STANDARD C3	27.2	69	35	167	5.6	35	11	808	3.30	59	27	2	22	28	25.4	17.0	23.5	82	.58	.096	22	173	.62	160	.085	21	1.80	.042	.17	15	1	4.8	1	.03	6

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data /- FA ____

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
351568	.3	31	23	62	.5	29	11	576	3.33	29	2	<2	4	19	.4	<.5	<.5	22	.30	.076	27	22	.33	81	.006	1	1.13	.004	.09	1	<1	2.7	<1	.02	2
351569	.4	34	26	64	.5	35	14	766	3.78	33	2	<2	5	13	.4	<.5	.8	25	.15	.069	30	25	.35	76	.007	2	1.22	.005	.08	1	<1	3.0	<1	.01	2
351572	<.2	31	28	69	.2	31	11	374	3.91	32	1	<2	6	8	.5	<.5	<.5	29	.09	.044	33	27	.35	111	.007	1	1.32	.005	.11	2	<1	2.1	1	<.01	3
351573	.4	31	25	63	.2	31	15	421	3.66	38	1	<2	9	6	.4	.5	<.5	21	.06	.028	36	21	.31	52	.013	2	.95	.003	.05	2	<1	1.9	<1	<.01	2
351574	.6	22	29	59	.3	24	14	436	3.23	33	1	<2	5	10	.3	.5	1.3	23	.13	.047	29	19	.26	70	.005	<1	1.07	.004	.06	2	<1	1.7	<1	<.01	2
351575	.8	25	25	57	.3	24	9	223	5.25	43	1	<2	7	5	.2	.5	1.3	28	.04	.036	31	24	.27	51	.007	<1	1.08	.003	.04	2	<1	1.5	<1	.01	4
351576	.7	27	26	66	.3	30	17	1997	4.00	36	2	<2	3	17	.5	.5	.7	31	.21	.059	31	23	.25	96	.012	<1	1.09	.005	.08	3	<1	1.8	1	.01	4
351577	.7	30	12	63	.2	24	11	294	3.10	22	1	<2	8	8	.3	1.1	<.5	14	.09	.043	48	7	.04	39	.005	<1	.32	.003	.04	1	<1	1.1	<1	<.01	1
351578	.8	24	38	45	.5	24	10	698	3.12	32	2	<2	2	16	.3	<.5	1.6	23	.21	.056	31	16	.22	65	.006	<1	.93	.004	.06	1	<1	1.8	<1	.01	3
351579	1.1	66	39	76	1.5	51	30	2122	5.32	57	5	<2	4	27	.7	.5	1.7	26	.37	.128	32	25	.20	91	.009	2	1.36	.006	.11	2	<1	4.2	<1	.03	5
351580	.6	15	19	43	.1	14	7	283	3.03	26	<1	<2	5	5	<.2	<.5	.5	28	.03	.027	34	16	.13	53	.014	<1	.82	.002	.04	1	<1	1.3	<1	<.01	3
351581	1.0	70	66	68	.7	64	31	1045	4.36	71	4	<2	6	18	.6	2.2	3.3	13	.17	.078	37	12	.15	42	.005	<1	.71	.003	.05	3	<1	3.1	1	.01	2
351582	.6	15	15	45	.3	17	6	239	2.69	20	<1	<2	2	6	<.2	1.0	<.5	26	.05	.046	29	15	.14	73	.008	<1	.76	.004	.05	1	<1	1.0	<1	.01	3
351583	.6	21	15	70	.2	22	10	544	4.43	24	1	<2	5	5	.4	<.5	<.5	35	.05	.052	24	26	.18	72	.009	1	1.31	.005	.06	14	<1	1.7	<1	.01	5
351584	.4	28	22	60	.1	29	12	295	4.01	53	1	<2	10	4	.5	<.5	.7	20	.02	.031	37	23	.31	58	.006	<1	1.12	.002	.05	2	<1	1.9	<1	<.01	3
RE 351584	.5	27	22	58	.1	29	12	285	3.87	53	<1	<2	10	4	.5	.5	.7	18	.02	.030	35	22	.30	56	.006	<1	1.09	.002	.04	2	<1	1.7	1	<.01	3
351587	.3	32	21	67	.2	36	15	601	3.68	32	2	<2	4	18	.5	<.5	.5	32	.25	.061	29	34	.45	101	.009	1	1.29	.005	.08	1	<1	2.9	<1	.01	4
351589	.2	41	26	69	.9	41	16	763	3.90	40	3	<2	5	20	.5	.5	.8	29	.25	.082	28	30	.40	123	.007	<1	1.41	.006	.10	2	<1	3.5	<1	.02	4
351590	.4	38	25	72	.9	40	16	655	3.94	41	2	<2	5	18	.5	.5	.8	28	.23	.079	29	30	.41	118	.007	1	1.40	.005	.10	1	<1	3.3	<1	.02	4
351591	.3	37	24	64	.2	40	15	638	3.76	38	2	<2	6	14	.4	<.5	<.5	29	.16	.059	34	29	.42	110	.008	1	1.41	.004	.10	2	<1	3.7	1	<.01	4
351592	.4	40	28	68	.4	38	15	813	4.06	36	2	<2	6	17	.5	.5	<.5	30	.21	.076	30	34	.42	130	.009	<1	1.54	.006	.14	1	<1	4.0	<1	.01	5
351594	.6	32	30	65	.4	31	15	643	3.52	55	1	<2	5	14	.6	.8	.6	27	.17	.058	33	23	.34	105	.008	<1	1.06	.005	.08	2	<1	2.7	<1	.01	3
351595	.5	45	44	86	.3	49	21	877	3.72	34	2	<2	11	103	.5	<.5	.6	20	2.19	.059	28	20	.47	74	.007	3	1.01	.008	.13	1	<1	3.4	<1	.03	4
351596	2.9	50	55	87	.4	55	21	957	4.63	63	3	<2	10	18	.6	.7	1.4	21	.27	.062	38	22	.28	91	.006	<1	.97	.005	.08	3	<1	3.5	<1	.01	4
STANDARD G-2	1.5	3	3	44	<.1	7	3	559	2.03	<1	3	<2	4	74	<.2	<.5	<.5	45	.68	.102	12	82	.62	231	.134	4	.95	.083	.48	3	<1	2.7	<1	<.01	4
STANDARD C3	27.3	71	36	171	5.6	36	11	814	3.33	59	26	2	23	30	24.6	15.7	23.1	85	.60	.096	23	182	.64	160	.093	24	1.83	.042	.17	15	1	4.7	<1	.02	6

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004440R Page 1

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: R. Hall

SAMPLE#	Au* ppb
00742	27.5
00743	70.6
00744	26.6
00745	98.4
00746	151.6
00747	149.6
00748	170.6
00749	56.2
00801	12.0
00802	130.5
00803	190.3
00805	91.1
00806	204.9
00807	231.3
00808	241.6
00809	202.1
00810	17.7
00811	15.4
00813	31.1
00814	24.9
00815	31.8
00816	21.6
00817	32.9
00818	520.0
RE 00818	1059.4
00883	14.6
00884	4.1
00885	1.3
00886	2.8
00887	1.3
00888	1.8
00890	1.0
00891	2.7
00892	6.9
STANDARD DS2	195.0

AU* BY ACID LEACHED, ANALYSIS BY ICP/MS. (10 gm)
- SAMPLE TYPE: SOIL PULP
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: NOV 16 2000 DATE REPORT MAILED: Nov 22/00 SIGNED BY: D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data FA

SAMPLE#	Au* ppb
00893	3.6
00894	14.4
00895	3.8
00896	11.5
00897	1.4
00898	1.4
00900	1.5
01016	.6
01017	9.7
01018	2.4
01019	1.7
01020	4.9
01021	3.0
01022	10.3
01023	5.3
01024	4.4
01025	5.4
01026	3.0
01027	2.9
01028	9.0
01029	9.0
01031	6.4
01032	23.4
01033	3.2
01034	2.0
01035	14.5
RE 01035	9.9
01036	7.8
01037	2.6
01038	2.2
01039	5.2
01040	4.9
01041	4.2
01042	5.9
STANDARD DS2	193.0

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data /~ FA ____

SAMPLE#	Au* ppb
01043	5.0
01044	6.1
01045	71.5
01046	8.8
01047	33.3
01049	480.9
01050	47.9
01051	98.1
01052	81.6
01054	149.9
01055	41.0
01056	15.2
RE 01056	36.4
01060	106.1
01061	50.6
01062	46.5
01063	110.0
01064	69.2
01065	20.7
01066	61.5
01067	30.5
01068	23.0
01069	4.6
01070	6.3
01071	2.1
01072	5.2
01073	35.9
01074	31.9
01075	15.8
01076	29.1
01077	20.2
01078	22.6
01079	66.8
01080	96.2
STANDARD DS2	189.1

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au* ppb
01081	21.8
01083	17.2
01084	97.5
01085	45.8
01086	47.1
01087	80.8
01088	59.9
01089	12.7
01090	30.2
01091	29.6
01092	219.6
01093	147.7
01094	31.5
01095	16.9
RE 01095	21.7
01096	187.0
01097	838.6
01098	305.1
01099	9.5
01100	2.9
01372	13.7
01375	5.0
01376	2.5
01377	5.3
01378	2.8
01379	2.2
01380	4.2
01381	1.9
01382	5.0
01383	1.9
01384	3.4
01385	5.4
01386	.8
01387	1.1
STANDARD DS2	193.0

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au* ppb
01388	2.5
01389	2.6
01390	1.6
01391	3.1
01392	1.5
01393	10.5
01395	10.2
01396	1.4
01397	3.6
01398	1.0
01399	2.1
01400	36.1
01601	1.0
01602	1.3
01603	3.3
01604	55.6
01605	4.8
01608	23.0
01611	12.5
01612	21.8
01613	8.4
01614	54.5
01615	13.9
RE 01615	17.1
01616	34.8
01617	2.8
01619	91.8
01620	332.4
01621	354.5
01651	7.5
01652	30.8
01653	29.5
01654	16.7
01655	42.4
STANDARD DS2	198.0

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Au* ppb
01656	26.8
01657	4.8
01658	107.4
01659	13.3
01660	14.1
01661	26.0
01792	70.4
01793	96.4
01794	46.2
01795	304.1
01796	27.3
01797	16.6
01798	15.9
01800	21.0
RE 01822	407.2
01822	465.8
01823	188.0
01824	207.7
01827	86.1
01828	179.2
01829	132.2
01830	140.2
01831	179.6
01832	84.9
01833	62.5
01834	69.7
01835	54.5
01836	169.6
01837	115.5
01838	138.9
01839	152.2
01840	242.4
01841	157.8
01842	75.3
STANDARD DS2	191.0

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

SAMPLE#	Au* ppb
01843	249.5
01844	133.1
01845	167.4
01846	13.4
01847	4.1
01848	9.7
01849	13.7
01850	18.3
01851	9.0
01852	165.1
01853	96.5
01854	155.4
01856	81.0
01857	129.3
01858	63.8
01859	206.1
01861	104.6
01862	41.2
01863	71.6
01864	45.9
01865	348.9
RE 01865	267.1
01866	42.7
01867	294.2
01868	189.6
01869	409.7
01870	426.5
01871	15.8
01872	11.1
01874	201.7
01875	28.8
01876	136.6
01877	44.1
01878	13.4
STANDARD DS2	201.0

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data __/__FA ____

SAMPLE#	Au* ppb
01879	22.1
01880	14.3
01881	6.1
01882	9.3
01932	7.3
01933	4.5
01934	3.6
01935	4.5
01936	19.6
01937	3.5
01938	8.1
01939	1.7
01940	4.4
01941	5.9
01942	2.9
01943	13.2
01945	76.5
RE 01945	39.1
01946	33.5
01947	3.6
01948	2.8
01949	20.0
01950	28.2
01951	10.0
01952	211.1
01953	54.8
01961	150.9
01962	295.9
351561	317.4
351562	477.2
351563	201.1
351565	23.2
351566	121.0
351567	38.4
STANDARD DS2	198.3

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au* ppb
351568	46.8
351569	73.0
351572	15.8
351573	67.1
351574	370.5
351575	158.7
351576	123.5
351577	20.9
351578	65.6
351579	49.2
351580	93.2
351581	179.5
351582	24.6
351583	21.2
351584	123.6
RE 351584	106.6
351587	56.9
351589	91.6
351590	110.4
351591	60.8
351592	36.2
351594	257.4
351595	75.6
351596	135.2
STANDARD DS2	190.0

Sample type: SOIL PULP. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

APPENDIX IX

ASSAY CERTIFICATES

PART 5 – ROCK SAMPLE / PROSPECTING / MISCELLANEOUS ASSAY CERTIFICATES

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002329
305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: R. Hall

SAMPLE#	Au** gm/mt
0448	5.41
0449	19.07
0450	16.19
0451	51.04
RE 0451	50.04
STANDARD AU-1	3.64

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: SLUDGE
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUL 13 2000 DATE REPORT MAILED: July 21/00 SIGNED BY. C. Leong .D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data A FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) 1-1/16
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002330

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: K. Ross

SAMPLE#	Au** gm/mt	Au** gm/mt
B 172201	.01	-
B 172202	.18	-
B 172203	5.48	7.93
B 172204	.34	-
B 172205	.02	-
B 172206	.15	-
RE B 172206	.14	-

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: ROCK
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUL 13 2000 DATE REPORT MAILED: July 21/00 SIGNED BY..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A002441

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: R. Hall

SAMPLE#	Au** gm/mt	Au** gm/mt	Au** gm/mt	Au** gm/mt
B 171001	<.01	-	-	-
B 171002	.01	-	-	-
B 171003	3.64	.57	2.81	1.24
B 171004	.02	1.85	.27	.03
B 171005	<.01	-	-	-
B 171006	<.01	-	-	-
B 171007	.03	-	-	-
B 171008	<.01	-	-	-
B 171009	<.01	-	-	-
B 171010	.01	-	-	-
B 171011	.02	-	-	-
B 171012	<.01	-	-	-
RE B 171012	<.01	-	-	-
B 171013	<.01	-	-	-
B 171014	<.01	-	-	-
B 171015	<.01	-	-	-
B 171016	<.01	-	-	-
B 171017	<.01	-	-	-
B 171018	<.01	-	-	-
B 171019	.09	-	-	-
B 171020	.02	-	-	-
B 171021	.03	-	-	-
B 171022	<.01	-	-	-
B 171023	<.01	-	-	-
B 171024	1.20	-	-	-
STANDARD AU-1	3.74	-	-	-

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: ROCK
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JUL 19 2000 DATE REPORT MAILED: Aug 3/00 SIGNED BY. C. Leong .D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003185

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: A. Justason

SAMPLE#	Au** gm/mt
B 171025	.02
B 171026	.03
B 171027	.01
B 171028	<.01
B 171029	<.01
B 171030	.01
B 171031	.02
B 171032	<.01
B 171033	.02
B 171034	.01
B 171035	.02
B 171036	2.38
B 171037	.04
B 171038	1.81
B 171039	14.57
B 171040	.02
RE B 171040	.05
B 171041	.04
B 171042	.12
B 171043	.01
B 171044	<.01
B 171045	.04
B 171046	<.01
B 171047	<.01
B 171048	.02
B 171049	.02
B 171050	.02
B 171358	<.01
B 171359	<.01
B 171360	.02
B 171361	<.01
STANDARD AU-1	3.60

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: ROCK R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: AUG 25 2000 DATE REPORT MAILED: Sept 2/00 SIGNED BY. C. Leong D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003186

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: A. Justason

SAMPLE#	Au** ppb
B 171351	96
B 171352	56
B 171353	136
B 171354	2
B 171355	36
B 171356	15
B 171357	12
STANDARD AU-S	45

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SOIL SS80 60C

DATE RECEIVED: AUG 23 2000 DATE REPORT MAILED: Sept 2/00 SIGNED BY. C. Leong .D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) 253-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. File # A003211
305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ken Lord

SAMPLE#	Au** gm/mt	Au** gm/mt
B 171362	.02	-
B 171363	.02	-
B 171364	55.41	58.30
B 171365	.14	-
RE B 171365	.14	-

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: ROCK R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: AUG 25 2000 DATE REPORT MAILED: Sept 6/00 SIGNED BY. . . . . B. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

REVISED COPY

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) 1-1716
(ISO 9002 Accredited Co.)

ASSAY CERTIFICATE

Int'l Wayside Gold Mines Ltd. File # A003394
305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ken Lord

SAMPLE#	Au** gm/mt
B 171366	<.01
B 171367	.50
B 171368	<.01
B 171369	.01
B 171370	.01
B 171371	.62
RE B 171371	.44

GROUP 6 - PRECIOUS METALS BY FIRE ASSAY FROM 1 A.T. SAMPLE, ANALYSIS BY ICP-ES.
- SAMPLE TYPE: ROCK R150 60C
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: SEP 6 2000 DATE REPORT MAILED: Sept 15/00 SIGNED BY. C. L. D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data F FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. File # A003395
305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Ken Lord

SAMPLE#	Au** ppb
B 171372	4

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SOIL SS80 60C

DATE RECEIVED: SEP 6 2000 DATE REPORT MAILED: Sept 15/00 SIGNED BY. C. Leong D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. File # A003588

305 - 455 Granville St., Vancouver BC V6C 1T1

SAMPLE#	Au** ppb
B 171399	82
B 171400	14
RE B 171400	11

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: ROCK R150 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: SEP 14 2000 DATE REPORT MAILED: Sept 21/00 SIGNED BY..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

SAMPLE#	Au** ppb
B 172288	<2
B 172289	6
B 172290	<2
B 172291	3
B 172292	4
B 172293	<2
B 172294	9
B 172295	3
B 172296	2
B 172297	2
B 172298	9
RE B 172298	4
B 172502	3
B 172503	6
B 172504	13
B 172505	8
B 172506	10
B 172507	4
B 172508	37
B 172509	14
B 172510	5
STANDARD AU-R	474

Sample type: ROCK R150 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ___ FA ___

ACME ANALYTICAL LABORATORIES LTD. (ISO 9002 Accredited Co.) 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) 253-1716

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003695 Page 1

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: R. Hall

SAMPLE#	Au** ppb
B 172251	74
B 172252	13
B 172253	15
B 172254	8
B 172255	92
B 172256	14
B 172257	<2
B 172258	24
B 172259	12
B 172260	9
B 172261	11
B 172266	<2
B 172267	13
B 172268	11
B 172269	<2
B 172270	2
RE B 172270	4
B 172271	8
B 172272	12
B 172273	3
B 172274	7
B 172275	11
B 172276	4
B 172277	8
B 172278	3
B 172279	3
B 172280	<2
B 172281	17
B 172282	<2
B 172283	12
B 172284	8
B 172285	<2
B 172286	<2
B 172287	13
STANDARD AU-R	476

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: ROCK R150 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: SEP 20 2000 DATE REPORT MAILED: Sept 28/00 SIGNED BY: D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003697

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: R. Hall

SAMPLE#	Au** ppb
B 172401	19
B 172402	24
B 172403	108
B 172404	260
B 172405	21
B 172406	10
B 172407	5
B 172408	39
B 172409	1195
B 172410	35
B 172411	4237
B 172412	655
RE B 172412	768
B 172413	59
B 172414	361
B 172415	184
B 172416	123
B 172417	182
B 172418	17
B 172419	8
B 172420	16
STANDARD AU-S	48

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SOIL SS80 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: SEP 20 2000 DATE REPORT MAILED: Oct 2/00 SIGNED BY. C. Leong D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO File # A003738

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Fran MacPherson

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm
B 172355	20	37	72	150	.3	46	7	286	13.23	1345	<8	3	<2	10	2.2	<3	13	4	.05	.255	1	20	.01	37	<.01	<3	.19	.01	.03	25
B 172356	<1	23	100	123	.7	32	15	2166	8.17	9	12	<2	3	213	.7	<3	<3	<1	10.38	.019	2	7	1.96	61	<.01	3	.13	.01	.06	3
B 172357	2	31	166	178	.6	49	23	1422	5.96	13	9	<2	9	19	.4	<3	<3	1	2.14	.041	9	10	.07	63	<.01	5	.31	.02	.13	<2
B 172358	<1	25	4	77	<.3	71	27	803	4.87	<2	<8	<2	6	12	<.2	<3	<3	2	.12	.041	15	15	.29	96	<.01	6	.55	.01	.14	3
B 172365	1	90	<3	143	<.3	406	65	1372	9.42	273	<8	<2	<2	201	.3	<3	<3	5	3.99	.111	3	166	3.24	54	<.01	<3	.42	.02	.18	3
B 172368	<1	3	79	<1	3.9	51	185	57	18.86	613	<8	51	<2	2	<.2	<3	132	1	.02	.003	<1	14	.01	6	<.01	<3	.01	.01	.01	6
B 172369	2	15	60	47	.3	25	11	519	2.83	8	<8	<2	12	14	<.2	<3	<3	3	.49	.040	24	16	.05	78	<.01	6	.36	.03	.22	2
B 172370	1	31	21	35	<.3	34	13	247	3.31	3	<8	<2	9	7	<.2	<3	<3	2	.05	.029	13	13	.10	62	<.01	8	.39	.02	.14	3
RE B 172370	<1	31	21	35	<.3	34	13	248	3.33	2	<8	<2	8	7	<.2	<3	<3	2	.05	.029	13	12	.10	63	<.01	7	.39	.02	.14	3
STANDARD C3	25	67	34	164	5.4	39	12	771	3.41	55	23	4	21	29	22.9	17	22	75	.57	.096	18	177	.63	148	.09	25	1.88	.04	.17	15

GROUP 1D - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: ROCK R150 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: SEP 25 2000 DATE REPORT MAILED: Oct 4/00 SIGNED BY: C. T. ..D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data___ FA___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO File # A003739

305 - 455 Granville St., Vancouver BC V6C 1T1 Submitted by: Fran MacPherson

SAMPLE#	Au** ppb
B 172352	2
B 172353	3
B 172354	5
B 172359	<2
B 172360	32
B 172361	4
B 172362	9
B 172363	2
B 172364	<2
RE B 172364	2
B 172371	12
B 172372	<2
B 172373	13

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SOIL SS80 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: SEP 25 2000 DATE REPORT MAILED: Oct 2/00 SIGNED BY. ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604) -1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A003833

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: R. Hall

SAMPLE#	Au** ppb
B 172366	4
B 172367	29
RE B 172367	26

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: ROCK R150 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: SEP 28 2000 DATE REPORT MAILED: Oct 4/00 SIGNED BY. C. Leong D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO File # A003983

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: Gary Poliachuk

SAMPLE#	Au** ppb
B 172374	49
B 172375	27
B 172376	218
B 172377	143
B 172378	241
B 172379	75
B 172380	108
B 172381	77
B 172382	237
B 172383	263
B 172384	67
B 172385	175
B 172386	33
RE B 172386	24
B 172387	13
B 172388	14
B 172389	163
B 172390	123
B 172391	381
B 172392	1049
B 172393	137
B 172394	394
STANDARD AU-S	47

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SOIL SS80 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 10 2000 **DATE REPORT MAILED:** Oct 16/00 **SIGNED BY.** C. Leong D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data /FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO File # A003984

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: Gary Poliachuk

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Au** ppb
B 172395	.5	40	56	40	.1	42	19	642	3.13	21	4	<2	9	16	<.2	<.5	.6	12	.16	.077	27	25	.06	123	.002	1	.62	.009	.17	2	<1	3.4	<1<.01	2	4

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: ROCK R150 60C AU** GROUP 3B - 30.00 GM SAMPLE ANALYSIS BY FA/ICP.

DATE RECEIVED: OCT 10 2000 DATE REPORT MAILED: Oct 23/00 SIGNED BY C. Leong D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data ✓ FA ___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. File # A004159

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: Gary Poliachuk

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Au** ppb
B 172604	.5	10	10	28	.2	36	19	655	5.53	3858	4	2	3	15	.7	4.6	5.2	4	.02	.012	10	27	.02	88	.001	1	.37	.004	.06	4	<1	2.7	<1	.03	<1	1681
B 172610	<.2	140	78	48	.5	15	11	2062	8.81	67	2	<2	<1	980	.2	<.5	1.0	4	26.17	.011	2	7	.84	8	<.001	3	.09	.007	<.01	1	<1	1.1	<1	1.26	2	11
B 172611	.4	195	19	75	.1	17	60	817	10.64	23	1	<2	6	72	<.2	<.5	1.5	103	2.30	.126	26	24	.75	58	.002	<1	1.86	.036	.07	1	<1	7.0	<1	5.65	6	8
RE B 172611	.4	190	19	75	.1	17	60	821	10.65	22	1	<2	6	71	<.2	<.5	1.5	104	2.29	.127	26	24	.75	58	.002	<1	1.88	.038	.07	1	<1	7.1	<1	5.69	6	8

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: ROCK R150 60C AU** GROUP 3B - 30.00 GM SAMPLE ANALYSIS BY FA/ICP.
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 18 2000 **DATE REPORT MAILED:** Oct 31/00 **SIGNED BY** ..... D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only. Data___ FA___

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. File # A004277
P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: Gary Poliachuk

SAMPLE#	Au** ppb
B 172398	64
B 172399	12
B 172400	237
B 172602	514
B 172606	499
B 172608	278
B 172609	14
B 172612	76
B 172613	8
B 172614	4
B 172615	7
RE B 172618	7
B 172616	122
B 172617	12
B 172618	2
B 172620	120
B 172621	25
B 172622	64
B 172623	97
B 172624	107
STANDARD AU-S	50

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SOIL SS80 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 23 2000 DATE REPORT MAILED: Nov 6/00 SIGNED BY. C. T. D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)
(ISO 9002 Accredited Co.)

1-1/16

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. File # A004278

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: Gary Poliachuk

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
172396	.7	6	59	17	.1	4	2	1342	2.16	8	1	<2	1	1320	<.2	.6	.9	<1	30.67	.025	4	2	1.22	15	<.001	4	.05	.012	.04	<1	<1	2.6	<1	.25	1
172397	3.6	2	2	1	.4	2	<1	33	.79	1711	<1	<2	<1	6	.7	1.1	18.2	1	.13	.001	1	22	.01	101	<.001	3	.01	<.001	<.01	9	<1	.5	<1	.38	<1
172601	4.1	31	2	43	<.1	33	7	142	4.19	516	1	<2	4	6	<.2	<.5	.5	9	.02	.072	14	20	.01	58	.001	3	.35	<.001	.07	3	<1	2.1	<1	.03	<1
172603	4.0	4	4	3	<.1	6	<1	130	.47	67	<1	<2	<1	2	<.2	.7	<.5	<1	.03	.001	<1	20	<.01	4	<.001	<1	.01	<.001	<.01	3	<1	.2	1	<.01	<1
172605	2.9	5	7	3	<.1	8	1	321	1.34	97	1	<2	<1	32	<.2	.6	1.6	<1	.72	.014	3	18	.04	9	<.001	1	.03	<.001	<.01	7	<1	.7	<1	.01	<1
172607	.6	48	7	36	<.1	517	44	2122	5.37	491	1	<2	1	594	.3	<.5	.8	8	13.01	.118	7	55	4.05	25	.001	3	.15	.007	.11	1	<1	6.4	<1	.19	1
RE 172607	.6	48	7	36	.1	520	46	2105	5.32	499	1	<2	2	591	.2	<.5	.6	11	12.92	.121	7	55	4.02	25	.001	4	.15	.009	.11	1	<1	6.4	<1	.21	1
172619	5.3	136	3153	63	4.0	7	1	726	1.35	89	3	<2	<1	10	.5	2.0	26.0	<1	.07	.104	1	23	.02	39	<.001	<1	.05	<.001	<.01	10	1	.2	1	.02	<1
172625	6.2	55	914	20	1.9	264	176	1550	11.94	334	5	3	2	20	.8	2.9	2549.0	10	.34	.235	8	87	.06	54	.001	<1	.20	<.001	.10	4	<1	2.2	<1	1.38	<1
172626	.9	20	31	108	.1	17	6	54	3.65	183	1	<2	3	6	.2	<.5	5.0	3	.02	.021	14	8	.01	48	<.001	1	.26	.010	.16	13	<1	1.9	1	1.11	<1
STANDARD C3	27.7	66	37	169	5.7	38	12	820	3.46	63	24	<2	19	32	23.3	15.0	24.2	83	.61	.102	22	184	.64	167	.091	27	1.85	.042	.17	15	1	4.8	<1	.03	7
STANDARD G-2	1.5	3	2	43	<.1	8	4	567	2.11	<1	3	<2	5	80	<.2	<.5	<.5	41	.72	.110	11	83	.64	245	.136	2	.93	.086	.50	3	<1	2.9	1	<.01	4

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: ROCK R150 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 23 2000 DATE REPORT MAILED: Nov 3/00 SIGNED BY: C. Leong .D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOO GOLD File # A004306

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: R. Hall

SAMPLE#	Au** ppb
B 172511	4
B 172512	2
B 172513	3
B 172514	2
B 172515	<2
B 172516	<2
B 172517	2
B 172518	<2
B 172519	4
B 172520	2
B 172521	2
B 172522	<2
RE B 172522	<2
B 172523	2
B 172524	<2
B 172525	3
B 172526	3
B 172527	2
B 172528	4
B 172529	6
B 172530	8
STANDARD AU-R	465

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: ROCK R150 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 24 2000 DATE REPORT MAILED: Nov 6/00 SIGNED BY. C. Leong D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEMICAL ANALYSIS CERTIFICATE

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOU File # A004438

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: Gary Polischuk

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm
B 172627	1.2	280	516	473	1.3	22	27	6008	10.04	243	<1	<2	<1	522	6.0	3.4	<.5	4	18.71	.097	1	4	4.73	11	<.001	<1	.01	.011	<.01	1	<1	16.4	3	.63	<1
B 172628	2.1	95	64	281	.4	49	20	4902	9.62	976	<1	<2	8	267	5.4	2.1	1.6	5	9.09	.039	25	10	2.76	35	.001	<1	.17	.009	.11	4	<1	8.7	2	3.76	1
B 172634	.6	545	27	70	<.1	51	26	5637	27.73	1436	1	<2	1	176	5.0	8.1	<.5	12	8.57	.015	3	4	1.55	21	.001	<1	.14	.004	.03	1	<1	1.2	<1	4.50	1
RE B 172634	.5	547	38	68	.1	49	25	5394	26.31	1588	1	<2	1	174	5.4	8.4	<.5	10	8.56	.015	3	3	1.48	21	.001	<1	.14	.004	.03	1	<1	1.2	<1	4.51	1
STANDARD C3	26.2	66	36	166	5.8	39	12	774	3.44	59	24	<2	21	29	24.5	18.1	23.2	84	.59	.098	18	172	.64	155	.088	23	1.91	.049	.17	15	2	4.5	1	.03	6
STANDARD G-2	1.5	2	3	44	<.1	8	4	528	2.08	<1	2	<2	4	85	<.2	<.5	<.5	43	.69	.105	7	77	.62	241	.133	<1	1.07	.145	.55	2	1	2.6	<1	<.01	4

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY OPTIMA ICP-ES.
UPPER LIMITS - AG, AU, HG, W = 100 PPM; MO, CO, CD, SB, BI, TH, U & B = 2,000 PPM; CU, PB, ZN, NI, MN, AS, V, LA, CR = 10,000 PPM.
ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
- SAMPLE TYPE: ROCK R150 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: NOV 1 2000 **DATE REPORT MAILED:** Nov/6/00 **SIGNED BY.** C. Leong D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE(604)253-3158 FAX(604)253-1716
(ISO 9002 Accredited Co.)

GEOCHEM PRECIOUS METALS ANALYSIS

Int'l Wayside Gold Mines Ltd. PROJECT CARIBOU File # A004439

P.O. Box 247, 2422 Barker, Wells BC V0K 2R0 Submitted by: Gary Polischuk

SAMPLE#	Au** ppb
B 172629	5
B 172630	7
B 172631	2
B 172632	51
B 172633	149
RE B 172629	3

GROUP 3B - FIRE GEOCHEM AU - 30 GM SAMPLE FUSION, DORE DISSOLVED IN AQUA - REGIA, ICP ANALYSIS. UPPER LIMITS = 10 PPM.
- SAMPLE TYPE: SOIL SS80 60C Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: NOV 1 2000 DATE REPORT MAILED: Nov 15/00 SIGNED BY. C. Leong D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.

Data FA

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 Brooksbank Ave., North Vancouver
British Columbia, Canada V7J 2C1
PHONE: 604-984-0221 FAX: 604-984-0218

To: STANDARD DRILLING & ENGINEERING LTD. ##

203 - 455 GRANVILLE ST.
VANCOUVER, BC
V6C 1T1

Project : CGQM
Comments: ATTN: FRANK CALLAGHAN

Page Number :2
Total Pages :3
Certificate Date: 19-SEP-97
Invoice No. :19742279
P.O. Number :
Account :KPS

Goldfinch Grid

CERTIFICATE OF ANALYSIS A9742279

SAMPLE	PREP CODE		Au ppb FA+AA
L150N 25E	201	202	40
L150N 50E	201	202	30
L150N 75E	201	202	15
L150N 100E	201	202	10
L150N 125E	201	202	10
L150N 150E	201	202	40
L150N 175E	201	202	10
L150N 200E	201	202	10
L150N 225E	201	202	15
L150N 250E	201	202	15
L150N 275E	201	202	40
L150N 300E	201	202	20
L200N 0E	201	202	40
L200N 25E	201	202	40
L200N 50E	201	202	270 ✓
L200N 75E	201	202	50 ✓
L200N 100E	201	202	45
L200N 125E	201	202	65 ✓
L200N 150E	201	202	50 ✓
L200N 175E	201	202	30
L200N 200E	201	202	20
L200N 225E	201	202	10
L200N 250E	201	202	20
L200N 275E	201	202	20
L200N 300E	201	202	15
L250N 0E	201	202	20
L250N 25E	201	202	60 ✓
L250N 50E	201	202	70 ✓
L250N 75E	201	202	35
L250N 100E	201	202	30
L250N 125E	201	202	20
L250N 150E	201	202	15
L250N 175E	201	202	25
L250N 200E	201	202	20
L250N 225E	201	202	10
L250N 250E	201	202	10
L250N 275E	201	202	10
L250N 300E	201	202	15
L300N 0E	201	202	40
L300N 25E	201	202	50 ✓

CERTIFICATION: [signature]

GOLDFINCH SOILS

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 Brooksbank Ave., North Vancouver
British Columbia, Canada V7J 2C1
PHONE: 604-984-0221 FAX: 604-984-0218

Gold Finch. Grid

To: STANDARD DRILLING & ENGINEERING LTD. ##

203 - 455 GRANVILLE ST.
VANCOUVER, BC
V6C 1T1

Project : CGQM
Comments: ATTN: FRANK CALLAGHAN

Page Number :1
Total Pages :3
Certificate Date: 19-SEP-97
Invoice No. :I9742279
P.O. Number :
Account :KPS

CERTIFICATE OF ANALYSIS A9742279

SAMPLE	PREP CODE		Au ppb FA+AA
L00N 0E	201	202	35
L00N 25E	201	202	500
L00N 50E	201	202	150
L00N 75E	201	202	20
L00N 100E	201	202	10
L00N 125E	201	202	35
L00N 150E	201	202	15
L00N 175E	201	202	10
L00N 200E	201	202	35
L00N 225E	201	202	30
L00N 250E	201	202	20
L00N 275E	201	202	25
L00N 300E	201	202	40
L50N 0E	201	202	30
L50N 25E	201	202	20
L50N 50E	201	202	15
L50N 75E	201	202	2220
L50N 100E	201	202	25
L50N 125E	201	202	60
L50N 150E	201	202	40
L50N 175E	201	202	10
L50N 200E	201	202	25
L50N 225E	201	202	35
L50N 250E	201	202	90
L50N 275E	201	202	50
L50N 300E	201	202	30
L100N 0E	201	202	60
L100N 25E	201	202	60
L100N 50E	201	202	130
L100N 75E	201	202	230
L100N 100E	201	202	130
L100N 125E	201	202	25
L100N 150E	201	202	70
L100N 175E	201	202	25
L100N 200E	201	202	20
L100N 225E	201	202	30
L100N 250E	201	202	[illegible]
L100N 275E	201	202	50
L100N 300E	201	202	35
L150N 0E	201	202	120

27 > 50 ppb.

CERTIFICATION: [signature]

Gold Finch Soils.

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 Brooksbank Ave., North Vancouver
British Columbia, Canada V7J 2C1
PHONE: 604-984-0221 FAX: 604-984-0218

& 1st Hump Lines

To: STANDARD DRILLING & ENGINEERING LTD. ##

203 - 455 GRANVILLE ST.
VANCOUVER, BC
V6C 1T1

Project : CGQM
Comments: ATTN: FRANK CALLAGHAN

Page Number :3
Total Pages :3
Certificate Date: 19-SEP-97
Invoice No. :I9742279
P.O. Number :
Account :KPS

CERTIFICATE OF ANALYSIS A9742279

SAMPLE	PREP CODE	Au ppb FA+AA
L300N 50E	201 202	50
L300N 75E	201 202	255
L300N 100E	201 202	335
L300N 125E	201 202	80
L300N 150E	201 202	90
L300N 175E	201 202	40
L300N 200E	201 202	20
L300N 225E	201 202	15
L300N 250E	201 202	25
L300N 275E	201 202	25
L300N 300E	201 202	15
1-H L10W 16+00N	201 202	< 5
1-H L10W 16+25N	201 202	< 5
1-H L10W 16+50N	201 202	< 5
1-H L10W 16+75N	201 202	< 5
1-H L10W 17+00N	201 202	< 5
1-H L10W 17+25N	201 202	15
1-H L10W 17+50N	201 202	5
1-H L10W 17+75N	201 202	5
1-H L10W 18+00N	201 202	< 5
1-H L10W 19+00N	201 202	55
1-H L10W 19+25N	201 202	20
1-H L10W 19+50N	201 202	4640
1-H L10W 19+75N	201 202	8200
1-H L10W 20+00N	201 202	100
1-H 11W 16+25N	201 202	20
1-H 11W 16+50N	201 202	10
1-H 11W 16+75N	201 202	< 5
1-H 11W 17+00N	201 202	< 5
1-H 11W 17+25N	201 202	20
1-H 11W 17+50N	201 202	5
1-H 11W 17+75N	201 202	< 5
1-H 11W 18+00N	201 202	< 5
1-H 11W 18+25N	201 202	< 5
1-H 11W 18+50N	201 202	< 5
1-H 11W 18+75N	201 202	< 5
1-HL10+25W16+00N	201 202	5
1-HL10+50W16+00N	201 202	< 5
1-HL10+75W16+00N	201 202	< 5
1-HL11+00W16+00N	201 202	< 5

(4)

CERTIFICATION: [signature]

GOLDFINCH & 1ST HUMP SAMPLES

APPENDIX X

BIBLIOGRAPHY

Published References

Bowman, A.
1889: Report on the geology of the mining district of Cariboo, British Columbia; Geological Survey of Canada, Annual Report for 1887-1888, v. 3, pt. 1, p. 1-49c.

1895: Maps of the principal auriferous creeks in the Cariboo mining district, British Columbia; Geological Survey of Canada, Maps 364-372.

Hanson, G.
1935: Barkerville gold belt, Cariboo district, British Columbia; Geological Survey of Canada, Memoir 181.

Johnston, W.A. and Uglow, W.L.
1926: Placer and vein gold of Barkerville, Cariboo District, British Columbia; Geological Survey of Canada, Memoir 149.

Knight, J. and McTaggart, K.C.
1989: Lode and placer gold of the Coquihalla and Wells areas, British Columbia; (92H, 93H); British Columbia Geological Survey Branch, Exploration in British Columbia 1989, p. 105-118.

Levson, V.M., and Giles, T.R.
1993: Geology of Tertiary and Quaternary Gold-Bearing Placers in the Cariboo Region, British Columbia (93A, B, G, H); British Columbia Geological Survey Branch, Bulletin 89.

Struik, L.C.
1986: Imbricated terranes of the Cariboo Gold belt with correlations and implications for tectonics in southeastern British Columbia; Canadian Journal of Earth Sciences, v.23, p. 1047-1061.

1988: Structural geology of the Cariboo Gold Mining District, east-central British Columbia; Geological Survey of Canada, Memoir 421.

Sutherland Brown, A.
1957: Geology of the Antler Creek area, Cariboo District, British Columbia; British Columbia Department of Mines and petroleum Resources, Bulletin 38.

Private Reports

Bolin, D.S., 1984: Golder Associates, June 20th, Report to Wharf Resources Ltd. On the Cariboo Gold Quartz Mine, Wells, British Columbia, Canada; 17 pp., Wharf Resources Ltd.

Hall, R.D., 1997: International Wayside Gold Mines Ltd. August 1st, Cariboo Gold Project at Wells, British Columbia

Laird, A. 1988 Cariboo Gold Quartz Property, 1988 Work Program Summary Report Prepared for Pan Orvana Resources Ltd.

Laird, A. 1989 Cariboo Gold Quartz Property, 1989 Work Program Summary Report Prepared for Pan Orvana Resources Ltd.

Lord, K. and Reid, R. 1997: Geochemical Survey and Prospecting Report for Assessment, Cariboo Gold Project at Wells BC.