

Bright Star Ventures Ltd.

Summary of Exploration Activities

on the BJP 1, BJP 2, BJP 3 Claims

MINERAL TITLES BRANCH Rec'd. JUL - 4 2003 L.I.# _____ File _____ VANCOUVER, B.C.

for the Period

from July 1st to December 15th, 2002

RECEIVED GOVERNMENT AGENT PENTICTON JUN 30 2003 NOT AN OFFICIAL RECEIPT TRANS # _____

June 27th, 2003

William Yeomans, P. Geo.

**GEOLOGICAL SURVEY BRANCH
ASSESSMENT REPORT**

27,189

Table of Contents

1.0	Introduction
2.0	Property Location and Access
3.0	Previous Work
4.0	Regional Geology
5.0	Property Geology – Alaskan-Type Ultramafic Complexes
5.1	Mafic Intrusives
5.1a	Gabbros
5.2	Ultramafic Rocks
5.2a	Olivine Clinopyroxenite
5.2b	Hornblende Clinopyroxenite
6.0	Soil Geochemistry Survey Results
7.0	Discussion of Soil Geochemistry
8.0	Conclusions and Recommendations
9.0	References

List of Figures

- Figure 1** **1:250,000 Scale Location Map**
- Figure 2** **1:100,000 Scale Claim Map**
- Figure 3** **Geological Setting of the Tulameen Complex**
- Figure 4** **Tulameen Complex – General Geology**
- Figure 5** **General Geology and Soil Sample Locations**
- Figure 6a** **Grid 2_3 : B-Horizon Cu (ppm) in Soils**
- Figure 6b** **Grid 2_3 : B-Horizon Au (ppb) in Soils**
- Figure 6c** **Grid 2_3 : B-Horizon Pd (ppb) in Soils**
- Figure 6d** **Grid 2_3 : B-Horizon Pt (ppb) in Soils**

List of Tables

- Table 1** **List of Claims**

Appendices

- Appendix A** **Summary of Expenses – Grid 2_3**
- Appendix B** **Eco Tech Assay Results – 2_3**
- Appendix C** **Statement of Qualifications**



Bright Star Ventures Ltd.
 Tulameen Ultramafic Complex

Figure 1
 Location Map

Similkameen Mining Division NTS 092H
 Scale 1:250,000

1.0 Introduction

Bright Star Ventures Ltd. optioned the BJP 1, BJP 2, and BJP 3 claims during 2001 in order to evaluate the mineral potential of the Tulameen ultramafic complex. These claims occur in the Similkameen Mining Division, located approximately 21.5 kilometers west of the town of Princeton, in South Central British Columbia. These claims were optioned from Cusac Gold Mines, who hold a joint venture agreement with Aboriginal Investments Ltd. This property was subjected to a regional B-horizon soil geochemistry survey during the period from July 1st till August 30th, 2002. This report describes the results of the survey.

2.0 Property Location and Access


The Tulameen ultramafic complex is located in the Cascade Mountains of southwestern British Columbia, approximately 26 kilometers northwest of the town of Princeton, B.C. The property is located on 1:20,000 scale NTS mapsheet M092H046, centered at approximately 49 degrees - 27' - 48" north latitude and 120 degrees - 48' - 34" west longitude. Access to the property is via a 16 km paved road from Princeton to Coalmont and then branching off to the south on the all-season Granite Creek road to seasonal logging roads that go to the headwaters of Blakeburn Creek. Elevations in the area range from approximately 3,000 feet asl along the Tulameen River valley, to more than 5,000 feet asl on Olivine Mountain. Major tributaries within the Tulameen River basin in the area of interest include Olivine, Granite and Blakeburn Creeks.

The majority of the property is covered by mature fir forest, although it is logged out in many areas. Forested areas are generally covered by glacial till. Glaciofluvial deposits have also been observed at lower elevations in the river valley. Non-glacial features include massive outcrops with little or no soil development, talus slopes and fluvial terraces. The region lies in a transition zone between the Cascade Mountains to the west and the Interior Plateau, located further to the east.

The climate is transitional between that of the dry southern interior and the much moister Cascade and Coast Mountain ranges located to the west. Summers are hot and dry while winters are cold with heavy snowfall at high elevations. Patches of snow can remain on the plateau areas of Olivine and Grasshopper Mountain until early June, and snowfalls can take place as early as mid-September. Figure 1 is a 1: 250,000 scale property location map for the BJP 1, 2, and 3 claims in the Tulameen area that were optioned in 2001 by Bright Star Ventures Ltd., while Figure 2 is a more detailed claim map of the property.

Table 1 is a list of Claims for the property:

Figure 2. Bright Star Ventures Ltd. Claim Map



LEGEND

-  Access Roads
-  Tulameen River
-  BSV Claim Map
-  NAD 83

Map Sheets 092H047
092H057, 92H046 and
092H056



Scale 1:100,000

Table 1. List of Claims

Claim Name	Mining Division	Tenure No.	Owner No.	Map No.	Work Till	Units	Tag No.
BJP 1	Similkameen	365092	141036	092H046	20041215	18	231263
BJP 2	Similkameen	365423	141036	092H046	20041215	20	231265
BJP 3	Similkameen	365442	1410361	092H046	20041215	15	231264

3.0 Previous Work

One of the earliest gold rushes in Canadian history occurred along the Tulameen River and its tributaries during the summer of 1885. During that year, John Chance discovered coarse visible gold in surficial gravels along Granite Creek near the confluence with the Tulameen River. By October of that year the town of Granite City had grown to a population of 2000 people. Granite Creek was staked over a length of five miles to the south from the Tulameen River and sixty-two companies had alluvial mining operations.

During the late 1800's the Tulameen District was the most important producer of platinum in North America. Platinum was recovered with the placer gold from the Tulameen River and her tributaries, including Granite, Cedar, Slate, Britton and Lawless Creeks. The platinum occurred as a fine, hard, silver-white lustrous metal with a high specific gravity in the sluice boxes and gold pans, along with the gold and heavy concentrations of black sands (magnetite and chromitite). In some areas there was more platinum than gold in the concentrates. Platinum nuggets up to 0.5 ounces were found, and during the year 1888, 1,500 ounces of platinum was recovered. This gold / platinum rush subsided over the following ten years, and in 1907 a fire razed the town of Granite City, leaving only a few buildings remaining and abandoned at this time. Total platinum production from the alluvial operations was estimated to be approximately 20,000 ounces from the area between 1885 and 1934 (O'Neil and Gunning, 1934).

Preliminary geological investigations by government agencies in the Tulameen area included work by Kemp (1902) who examined the geological relationship between the alluvial platinum occurrences and the surrounding ultramafic rocks for the U.S. Geological Survey, while Camsell (1913) conducted several years of geological study of the Tulameen area for the Geological Survey of Canada. Poitevin (1924) examined similarities between the platinum-bearing rocks of the Tulameen area with similar ultramafic complexes that occur in the Ural Mountains of Russia.

O'Neill and Gunning (1934), Rice (1948), and Eastwood (1959) also made significant contributions to understanding the geological setting for platinum mineralization in the Tulameen area. Findlay (1969) conducted detailed petrological and geological studies and identified platinum minerals in bedrock during the course of his Ph. D. research on the Tulameen ultramafic complex. He established an association between chromite and platinum values in the central core of the intrusion. The mineralogical, geochemical, and petrological associations relative to the distribution of platinum group elements in the

complex were also studied and documented by St. Louis (1982, 1986), and more recently by Rublee (1986, 1994).

Evenchick et. al., 1986, Nixon (1987, 1988, 1990,), and Nixon and Rublee (1987) classified the Tulameen Alaskan-type ultramafic complex as potential hosts for commercially exploitable deposits of platinum metals. The structural setting of this complex was documented and compared with other Alaskan-type ultramafic intrusions in Alaska and the Ural Mountains in Russia.

Nixon et. al.(1989), were able to trace the source of platinum nuggets in the Tulameen River to chromitite horizons within the dunite core of the Tulameen ultramafic complex by matching the phase chemistry of the gangue minerals spinel and olivine, in both alluvial nuggets and bedrock lode occurrences. Outcrops of dunite within the Tulameen ultramafic complex were metallurgically tested for the economic potential of the industrial mineral olivine. The Foundry Section of the Physical Metallurgy Research Laboratories in Ottawa (CANMET) conducted several tests on unaltered dunite samples. White (1987) reported that initial test results from the CANMET research were encouraging and that there is economic potential for the industrial mineral olivine on Grasshopper Mountain. These conclusions were based upon the results from coarse fractions ranging from 1.5 inches to 4.5 inches in size.

South of the Tulameen River, the ultramafic complex has been subjected to sporadic exploration programs for platinum group metals, iron, base metals and gold. Exploration companies and individual prospectors completed soil geochemistry surveys, ground magnetic, VLF-EM-16 geophysics and a very limited amount of diamond drilling. This area represents approximately 75% of the entire Tulameen ultramafic complex, yet it has remained highly under-explored to date. Poor access into this part of the complex inhibited the amount of exploration conducted in this part of British Columbia.

Early mineral exploration over the southern half of the complex commenced during the 1960's, with Fort Reliance Minerals Limited conducting prospecting, geological mapping and trenching over the ultrabasic rocks on four blocks of claims (Blocks A, B, C, and D) covering Olivine Mountain, Tanglewood Hill, and two areas located south and west of Lodestone Mountain. Exploration was directed towards copper and nickel occurrences, and several copper showings were discovered during this period. Two trenches were excavated on Claim Block "C", on claims FRM 92 and FRM 99, which are situated near the southern limit of the complex between Newton Creek and Arrastra Creek. Trench mapping and sampling revealed greater than 1% copper over widths of 6 meters. North to northwest trending fracture zones within hornblende clinopyroxenite control the strike of sulfide mineralization. A "shattered zone" and minor quartz veining was plotted on the trench map, suggesting that there may have been brecciation and open space filling associated with the fracture system. Rhythmic layering was recognized in the clinopyroxenite. In the same report it was mentioned that Anaconda drilled a copper showing immediately south of Block "C", at a sulfide occurrence located along Arrastia Creek, near the very southern limit of the Tulameen ultramafic complex during this same period.

Inter Canadian Development Corp. optioned the Lode I, III and IV claim groups and earned a 90% interest in the Lode II claim block (20 units). Allen (1987) collected 229 soil, silt and rock samples along three widely spaced reconnaissance lines. Soil samples were collected from B-Horizon soils from a depth of 20 to 40 centimeters every 50 meters. A Scintrex MP Proton magnetometer instrument was used to conduct a magnetometer survey along the same widely spaced lines. Allen (1987) noticed a broad general increase in magnetic readings towards the eastern margin of the complex. Allen and Brownlee (1989) conducted additional geophysical surveys over the area in 1988 and identified four VLF-EM-16 conductors within mafic to ultramafic rocks. Three of the four conductors are present on the BJP #1 claim block.

Two of the four conductors were spatially associated with elevated platinum, palladium, copper, nickel and chromium values in B-horizon soils that were collected during that program. During the next year follow-up B-horizon soil surveys confirmed the elevated and anomalous values that were obtained during the initial survey (Allen and Brownlee, 1989).

In late 1998 Aboriginal Investments acquired a 100% interest in claims BJP 1,2 and 3 which covered 53 units. Perry (1999) collected anomalous bedrock samples, mostly from outcroppings located within 200 meters of the overburden-covered VLF-EM-16 conductors. Values ranged up to 315 ppb Pt and 633 ppm Ni in fine-grained magnetite-rich hornblende pyroxenite. Some minor malachite staining was observed and sampled in the vicinity of the east-central conductor and slightly elevated Pt and Pd values were detected at the lab.

Lloyd Geophysics was hired to confirm the locations of the VLF-EM-16 anomalies and six trenches were demarcated in order to excavate and identify the cause for the electromagnetic anomalies. Thirteen B-horizon soils samples and 18 A-horizon humus soil samplers were collected and submitted for Pt-Pd-Au-Cu-Cr-Ni along with other elements which were analyzed by conventional fire assay, graphite furnace AA and multi-element ICP methods. Slightly elevated values of Pd and Cu in B-horizon soils were obtained in both the B-horizon soils and the humus samples in the vicinity of the east-central conductor. Highly anomalous Co and Ni values were obtained from A-horizon humus samples taken over the western conductor (See compilation map located in back pocket).

Trenches ranging in length from 35 to 80 meters in length and 0.5 to 5 meters in depth were excavated over the conductors using a JD 790 excavator. The east-central conductor was exposed in three separate trenches and a pyrite-bearing shear zone was exposed. Occasional malachite and a coarse grained cumulate pegmatite enriched in chalcopyrite was exposed. Sampling returned values up to 1.5% Cu, 50 ppb Au, 4600 ppb Ag and 30 ppb Pd in the cumulate pegmatite and in narrow, copper-rich quartz veins. Other anomalous Pt values were obtained within the excavated trench over the western conductor in magnetite-rich pyroxenite.




Figure 3. Geological setting of the Tulameen complex in relation to tectonostratigraphic terranes (modified after Kleinspehn, 1985). From Nixon and Rublee (1988)

4.0 Regional Geology


Nixon and Rublee (1988) have reported that Alaskan-type ultramafic complexes in British Columbia are potential hosts for exploitable deposits of platinum metals. The Tulameen ultramafic complex is situated immediately west of the juncture between the Quenellia tectonostratigraphic terrane with the Mount Lytton complex, and is situated within the southwestern Intermontaine Belt. Early tertiary "trans-tensional" block faulting related to regional right-lateral transform movement that has taken place along the Fraser River – Straight Creek fault system (Monger, 1985).

The Tulameen ultramafic complex (TUC) covers an area of 64 square kilometers, which makes it the largest of all Alaskan-type ultramafic complexes that occur within the Intermontaine Belt. The TUC extends north-northwest for 20 kilometers between Grasshopper Mountain and Arrastrada Creek in the south, parallel to the contact between Upper Triassic Nicola Group volcanics and metasedimentary rocks, and the granitic terrane of the Eagle Plutonic complex located to the west. The Nicola Group volcanic host rocks in this region are generally intermediate to felsic in composition and belong to the western facies of the Upper Triassic Nicola volcanic assemblage (Nixon and Rublee, 1988). This assemblage has undergone greenschist to amphibolite grade metamorphism.

The lithologies of the TUC are Early Jurassic, elongate ultramafic to gabbroic intrusive bodies. The Tulameen ultramafic assemblage was emplaced into the Upper Triassic Nicola Group during a late Triassic deformation event. During this time, Nicola group volcanics were folded along north to northwest trending fold axis (Findlay, 1969). Age dates for the complex yield a preferred age of 175 Ma (Mid-Jurassic), but this age may be erroneous due to argon loss during metamorphism. Preliminary age dates on the Eagle plutonic complex suggest an Early to mid-Cretaceous (97 to 120 Ma.) age of emplacement (Nixon and Rublee, 1988). The eastern margin of the TUC and its host Nicola volcanic assemblage are unconformably overlain by terrigenous metasedimentary and metavolcanic assemblages of the Early Tertiary (Eocene) Princeton Group along with Miocene plateau basalt flows.

Regional structures include major faults trending north-northwest and are characterized by a westward dipping foliation that parallels the eastern margin and extends into the Mount Lytton Batholith (also known as the Eagle Plutonic Assemblage) (Figure 3). The TUC displays a crude lop-sided concentric arrangement of a central dunite core surrounded by olivine clinopyroxenite, hornblende clinopyroxenite, and gabbroic rocks. The tectonic history during the emplacement of the TUC intrusive assemblage was complex and a multiple stage event. Figure 4 is a map of the general geology of the Tulameen ultramafic complex, with major structures and geological units identified relative to Bright Star Ventures claims. The original version of this map was initially prepared by Findlay (1969) as part of his Ph. D. research, and was subsequently modified as a result of additional geological fieldwork completed by Nixon et. al.(1997). The digital work completed in this study has taken this map a step further through data aggregation and compilation of all the old surveys. All of the old exploration data is

Figure 4. Tulameen Ultramafic Complex - General Geology



Ref. Maps M092H046 and M092H056
 1983 North American Datum
 UTM Coordinate System - Zone 10 1:100,000

4 0 4 Kilometers

LEGEND

Intrusive Rocks

TERTIARY (Eocene)

Granodiorite

LATE JURASSIC TO MID-CRETACEOUS

Eagle Plutonic Complex

LATE TRIASSIC Tulameen Complex

Mafic Pegmatite

Syenodiorite

Gabbro

Undifferentiated mafic / ultramafic rocks

Hornblende Clinopyroxenite

Hornblende Olivine Clinopyroxenite

Olivine Clinopyroxenite

Dunite

Stratified Rocks

TERTIARY (Eocene)

Princeton Group : Shales, sandstones and conglomerates, coal seams and seat earths, laharic breccias, rhyolitic to basaltic lava flows

UPPER TRIASSIC

NICOLA GROUP

Metasedimentary and metavolcanic rocks

Metavolcanic Units

Marble

Mylonitic Rocks

Undifferentiated ductily deformed Nicola and ultramafic - mafic rocks

Claims : Bright Star Ventures Ltd.

Geology from British Columbia Geological Survey Branch
 BULLETIN 93 , Map 5, Geology of the Tulameen
 Alaskan-Type Complex, by G.T. Nixon et. al. , (1997)

being compiled and layered into GIS format for re-evaluation using digital maps and georeferenced orthophotos.

5.0 Property Geology—Alaskan-Type Ultramafic Complexes

The general structure of Alaskan-type ultramafic complexes is characterized by a crudely concentric outward zonation of rock types ranging from olivine-bearing to hornblende – rich or magnetite rich clinopyroxenites about a steeply dipping dunite core (Taylor, 1967). Typical cumulate minerals include forsteritic olivine, diopsidic augite, chromite and magnetite. Orthopyroxene is characteristically absent in Alaskan-type ultramafic intrusions, indicating an alkalic affinity. Gabbroic rocks are typically tholeiitic in composition, but in the case of the Tulameen, the gabbro complex is unique in composition since these rocks are classified as syenogabbros and syenodiorites Nixon et. al., 1997). The property geology of the Tulameen ultramafic complex is similar to other well-documented Alaskan-Type ultramafic complexes located along the southeast coast of Alaska and in the Ural Mountains of Russia.

The Union Bay complex in Alaska is a concentrically zoned mafic / ultramafic complex with a dunite core and pyroxenite shells outward to a gabbro margin. High-grade PGE samples at Union bay contain significant amounts of iron, chromium and titanium oxides. PGE mineralization includes Pt-Fe alloys, native osmium and hollingworthite. Exploration work to date on the Union Bay complex favors the pyroxenite units as the most promising favourable host lithology for PGE mineralization.

5.1 – Mafic Intrusives

5.1a Gabbros

Large gabbroic intrusives occur throughout the TUC, proximal to the eastern margin of the complex. Major exposures are prevalent on the Grasshopper 1 and 2, Amy #1 and #2 and the BJP 1 and 2 claims. Findlay (1969) classified the gabbros as syenogabbros and syenodiorites. These gabbros are commonly in contact with olivine clinopyroxenite and only rarely come in contact with dunite. Syenodiorite is restricted to the southeastern margin of the TUC where it is unconformably overlain by Princeton Group lithologies.

The essential minerals within the syenogabbros include plagioclase (andesine), clinopyroxene, hornblende and potassium feldspar, with accessory minerals including apatite, opaque minerals, minor biotite and sphene. Most of the exposures of gabbro are saussuritized, are pale to dark grey in colour, and medium grained. Layered gabbros are common (Figure 4) throughout the TUC, and preserve a wealth of layering features, including modal grading of plagioclase and ferromagnesian phenocrysts in which the density grading may be normal or reversed in different layers (Nixon and Rublee, 1988).

Erosional tectonic unconformities transect earlier layers, indicating that magmatic activity occurred during crystal settling which disturbed the freshly precipitated cumulate crystal layers. Stratigraphic tops for magmatic layering are up to the west and dip steeply west towards the central dunite core in the TUC. Breccia zones have been observed in the gabbro in outcrops exposed along the Tulameen River, with rounded to sub-rounded blocks enclosed in a medium grained, uniform gabbroic groundmass. Net-textured sulfide mineralization (pyrite) has also been observed in the same section, and in this area the pyrite also lines fractures.

5.2 - Ultramafic Rocks

5.2a Dunite


Outcrops of dunite within central core of the Tulameen complex are restricted to Grasshopper and Olivine Mountain, which is covered by the Grasshopper #1 and #2 claims. The dunite is generally medium to dark grey in colour when fresh. The primary mineralogy consists of up to 90% forsteritic olivine with accessory chromite and rare diopsidic augite. Alteration minerals occur along fractures, breccias and in shear zones, including serpentine, carbonate, magnetite and talc. The degree of serpentinization varies from less than 20% to more than 80 % of the rock. The most intense areas of serpentinization occur near the eastern margin of the complex. Chromitite and chrome spinel appear to be randomly distributed throughout the dunite as discrete layers, nodular masses and schlieren up to 1 meter in length and 6 centimeters in width. Microscopic platinum-iron alloy minerals associated with the chromite include isoferroplatinum, osmiridium, platiniridium and tulameenite (Hart, 1982).

Magnetite is disseminated throughout the dunite often forming thin, fine-grained bands or coarse aggregates. Generally the chromitite can be distinguished from magnetite by the difference in magnetic attraction, and the chromitite is generally coarser grained and has a granular sugary texture. High grade Pt mineralization was identified during the course of the Newmont exploration program on the Grasshopper claims in areas where the average Cr % ranged from 1.2 % to 17.42%

5.2b Olivine Clinopyroxenite

Olivine clinopyroxenite surrounds the dunite core of the TUC and is exposed on the Amy #1, Grasshopper #1, BJP1, BJP2 and BJP 3 claims. The fresh rock is medium to coarse grained and has a blotchy green and black appearance due to partially serpentinized olivine and deep green clinopyroxene. Sporadic pegmatitic phases contain crystals up to 8 centimeters across and olivine crystals locally form schlieren (Nixon and Rublee, 1988). Olivine clinopyroxenite is present on the southern half of claim BJP1.

Figure 5. B-Horizon Soil Geochemistry Survey Areas



LEGEND

-  Geochemistry Grid
-  Tulameen River
-  BSV Claim
-  NAD 83

Map Sheets 092H047
092H057, 92H046 and
092H056



Scale 1:100,000

Within the contact zone, the dunite locally encapsulates the olivine clinopyroxenite while in other areas the reverse relationship is preserved in outcrop, and the olivine clinopyroxenite encapsulates the dunite. Breccias occur within the olivine clinopyroxenite near the western contact of the dunite between Britton and Champion Creeks. Angular to rounded blocks of dunite, pyroxenite and interlayered dunite-pyroxenite are enclosed in a serpentinized pyroxene-rich groundmass. A similar breccia occurs on the eastern margin of the dunite. Contacts dip moderately to steeply south.

5.2c Hornblende Clinopyroxenite

Hornblende clinopyroxenite generally occurs along the periphery of the Tulameen ultramafic complex and is present on the Grasshopper #1, Amy #2, and BJP 1,2 and 3 claims. Fresh rock is medium to coarse grained and contains diopsidic augite, hornblende, and relatively abundant magnetite with accessory minerals including biotite, sulfides and apatite. Mineral foliations are observable in medium-grained varieties and amphiboles may reach up to 3 centimeters in length in coarse-grained varieties. Accessory biotite and apatite occur in 6-meter thick magnetite-rich horizons on the southern slopes of Tanglewood Hill. The magnetite-rich horizons can also occur as schlieren and podiform masses. Mafic pegmatites are preferentially distributed near the margins of hornblende clinopyroxenite bodies (Findlay, 1969). One of the mafic pegmatites was sampled and identified as containing significant PGE values, with heavy pyrite and chalcopyrite mineralization exposed in the vicinity of Hines Creek along the sheared eastern contact zone between hornblende clinopyroxenites of the TUC with Nicola Group metvolcanic rocks (Zastavnikovich, 1988).

6.0 Soil Geochemistry Survey Results

Soil survey work on the Grid 2-3 area was completed on the Amy #2, BJP 2 and BJP 3 claims (Figure 5). It should be noted that the Amy #2 claim was under option to Bright Star at the time of the survey but has been subsequently dropped and returned to the claimholder in good standing. Approximately 17 kilometers of reconnaissance grid lines were flagged between grids 2 and 3 in order to obtain coverage of the western contact of Tulameen ultramafic complex. A total of 329 samples were taken on lines spaced between 150 and 400 meters apart, at 50-meter stations along the lines. Due to the highly magnetic nature of the hornblende clinopyroxenite units on the western half of the grid, lines tended to curve as a result of compass errors during traverses across this unit.

Figure 6a. is a map of B-horizon gold in soils, which indicates some minor sporadic gold distribution within the gabbro. Values range as high as 110 ppb Au over the gabbro, while near the sheared contact zone along the western margin of the Tulameen complex there is also a slightly elevated gold signature.

Figure 6a. Grid 2-3
B-Horizon Au (ppb)
in Soils




Figure 6b. Grid 2-3
B-Horizon Pd (ppb)
in Soils




Figure 6c. Grid 2-3
B-Horizon Pt (ppb)
in Soils




Figure 6d. Grid 2-3
B-Horizon Cu (ppm)
in Soils




Figure 6b. demonstrates sporadic distribution of palladium in B-horizon soils throughout the gabbro, while in the olivine clinopyroxenite there is a well-defined soil anomaly on lines 6850N and 7150N between stations 8450E and 8650E, with values ranging up to 45 ppb Pd. This anomaly remains open to the northwest.

Figure 6c. indicates that the serpentized dunite is clearly anomalous as demonstrated on line 8950N. Several high soils values are present in the olivine clinopyroxenite as well, with soil values ranging as high as 130 ppb Pt. There is a good correlation with platinum and palladium in the olivine clinopyroxenite on lines 6850N and 7150N between 8450E and 8650E.

Figure 6d. indicates a NW extension of the Grid 2 copper anomaly in the gabbro, where a large area contains between 100 and 600 ppm Cu. Some of the highest copper values are also related to the sheared western margin of the Tulameen ultramafic complex.

8.0 Conclusions and Recommendations

Exploration costs for the soil survey are presented in Appendix A, while Assay certificates are presented in Appendix B. The soil geochemistry identified anomalous copper PGE values in B-horizon on the BJP 1,2 and 3 claims along the western margin of the Tulameen ultramafic complex. During the 2003 program, additional soil and rock sampling surveys, IP geophysics and diamond drilling will further test these anomalies. A 100,000. budget will be planned for additional work on the Grid 2_3 area in conjunction with the surrounding Bright Star Ventures properties.

9.0 References

- Camsell, Charles, 1912. Note on the Occurrence of Diamonds at Tulameen, and Scottie Creek near Ashcroft, B.C. Geological Survey of Canada, Summary Report, 1911, p.123 and 124.
- Camsell, Charles, 1913. Geology and Mineral Deposits of the Tulameen District. Geological Survey, Department of Mines, Ottawa, Memoir No. 26.
- Evenchick, C.A., Monger, J.W.H., and Friday, S.J. (1986): Potential Hosts of Platinum Group Element Concentrations in the Canadian Cordillera; Geological Survey of Canada Open File 1433.
- Findlay, D.C., 1969. Origin of the Tulameen ultramafic complex, Southern British Columbia. Canadian Journal of Earth Sciences, p. 399-425
- Monger, J.W.H., 1985. Structural Evolution of the Southwestern Intermontaine Belt, Ashcroft and Hope Map Area, British Columbia; in Current Research, Part A, Geological Survey of Canada, Paper 85-1A, pages 349 - 358.
- Monger, J.W.H., 1989 Geology, Hope, British Columbia. Geological Survey of Canada, Map 41-1989, Sheet 1, Scale 1:250,000.
- Nixon G.T. and Rublee, V.J., 1988. Alaskan-type Ultramafic Rocks in British Columbia: New Concepts of the Structure of the Tulameen Complex. B.C. Ministry of Energy Mines and Petroleum Resources, Geological Field Work, 1987, Paper 1988-1, p.281-294.
- Nixon, G.T., 1987. Geology and Precious Metal Potential of Mafic-Ultramafic Rocks in British Columbia; Current Progress. B.C. Ministry of Energy, Mines and Petroleum Resources, Geological Fieldwork 1989, Paper 1990-1, p.353-358.
- Nixon, G.T., 1988. Geology of the Tulameen Complex. B.C. Ministry of Energy, Mines and Petroleum Resources, Open File 1988-25, 94 pages.
- Nixon, G.T., Hammack, J.L., Ash, C.H., Cabri, L.J., Case, G., Connelly, J.N., Heaman, L.M., Laflamme, J.H.G., Nuttall, C., Paterson, W.P.E., and Wong, R.H., Geology and Platinum-Group-Element Mineralization of Alaska-Type Ultramafic-Mafic Complexes In British Columbia. British Columbia Ministry of Employment and Investment Energy and Minerals Division, Geological Survey Branch. Bulletin 93. 141 p. + maps
- Nixon, G.T., (1990). Geology and Precious Metal Potential of Mafic-Ultramafic Rocks in British Columbia: Current Progress; in Geological Fieldwork 1989, B.C. Ministry of Energy, Mines and Petroleum Resources, Paper 1990-1, pages 353-358
- ONEILL, J.J. and H.C.Gunning, 1934. Platinum and Allied Metal Deposits of Canada. Geological Survey of Canada, Economic Geology Ser., No.13, p. 22-25 and 89-99.

Rice, H.M.A., 1960. Geology and Mineral Deposits of the Princeton Map-Area, British Columbia. Memoir 243, Geol. Surv. Canada, 136p..

Roed, M.A., (1992). Geological Branch Assessment Report. Economic geology J and L Claims, Olivine Mountain, British Columbia for Richard Chapman, by Geoterrain Consultants, Foxview Management Limited, Kelowna, B.C. 45 p. + 12 Figures

Rublee, V.J., (1986). Occurrence and Distribution of Platinum Group Elements in British Columbia; B.C. Ministry of Energy, Mines and Petroleum Resources, Open File 1986-7, 94 pages.

Rublee, V.J., (1994). Chemical Petrology, Mineralogy and Structure of the Tulameen Complex, Princeton Area, British Columbia; M. Sc. Thesis, University of Ottawa, Ottawa, Ontario. 183 pages.

St. Louis, Robert M., 1982. Platinoids in the Tulameen Ultramafic Complex. In Geologic Field Work, 1981, B.C. Ministry of Energy, Mines and Petroleum, Geological Branch, Mineral Resource Division, p. 218 - 222.

St. Louis, R.M., Nesbitt, B.E., and Morton, R.D., 1986. Geochemistry of Platinum Group Elements in the Tulameen Ultramafic Complex, Southern British Columbia, Economic Geology, Volume 81, p.961-973.

Taylor, H.P. Jr., 1967. The Zoned Ultramafic Complexes of Southeastern Alaska; in ultramafic and related Rocks, P.J. Wyllie, Editor, John Wiley and Sons Inc., New York, pages 97 - 121.

Taylor, David P., 1986. Geological Assessment Report on the Hop 1-8 (2017-2024(9)), Lodestone Mountain, British Columbia, Similkameen Mining Division, for Gordon Webster and Platonia Developments Inc. Geological Assessment Report 15,106, 5p.

Taylor, David P., 1988. Geological Report on the Hop and J.R. Claims, Lodestone Mountain, British Columbia, Similkameen Mining Division, owned by Sun-Gold Developments International Corp. Geological Assessment Report 17,986., 16p.

White, G.V., 1987. Olivine Potential in the Tulameen Ultramafic Complex, 'Preliminary Report (92 H/10). B.C. Ministry of Energy, Mines and Petroleum Resources, Geological Fieldwork 1986, Paper 1987-1, pp. 303-307.

APPENDIX A

Summary of Expenses – Grid 2_3 Survey

For Period August 8th – September 20th, 2002

Assay Costs – Eco-Tech laboratories	7,913.03
Room and board – 3 men 15 days @ 25.00/day	1,125.00
Food – 3 men 15 days @ 35.00 per day	1,535.00
Salaries – 3 men 15 days @ 160.00 per day	7,200.00
1 BSV Geotech 15 days supervision @ 175.00/day	2,625.00
1 BSV Geotech – 15 days truck rental @ 65.00 /day	975.00

For Period December 16th-21st, 2002

1 Geologist - 6 days data compilation, report @ 375.00/day	2,250.00
--	----------

Total = \$23,623.03

APPENDIX B

BRIGHT STAR VENTURES
Suite 205-555 Burrard Street
Po Box 218
Vancouver, BC, V7X 1M7

23-Oct-02

Attention: Accounts Payable

2002 INVOICE

INVOICE #:AK 02-388

<i>DESCRIPTION</i>	<i>PRICE / SAMPLE</i>	<i>AMOUNT</i>
<i>PROJECT #: Tulameen</i>		
106 SAMPLE PREP (SOIL)	0.95	100.70
106 AU/PD/PT 30G PKG GEOCHEM	13.50	1431.00
106 MULTI-ELEMENT ICP	6.50	689.00
	SUBTOTAL:	<u>2220.70</u>
	& 7% G.S.T:	155.45
	TOTAL DUE & PAYABLE UPON RECEIPT:	<u><u>2376.15</u></u>

THANK YOU!!

G.S.T. REGISTRATION NUMBER R101565356

TERMS: NET 30 DAYS. INTEREST AT RATE OF 1 1/2 PER MONTH (18% PER ANNUM)
WILL BE CHARGED ON OVERDUE ACCOUNTS.

BRIGHT STAR VENTURES
Suite 205-555 Burrard Street
Po Box 218
Vancouver, BC, V7X 1M7

26-Sep-02

Attention: Accounts Payable

2002 INVOICE

INVOICE #:AK 02-326

<i>DESCRIPTION</i>	<i>PRICE / SAMPLE</i>	<i>AMOUNT</i>	
<i>PROJECT #: Tulameen</i>			
251 Soils Received - 4 No Samples			
247	SAMPLE PREP (SOIL)	0.95	234.65
247	AU/PD/PT 30G PKG GEOCHEM	13.50	3334.50
247	MULTI-ELEMENT ICP	6.50	1605.50
	SUBTOTAL:		5174.65
	& 7% G.S.T:		362.23
	TOTAL DUE & PAYABLE UPON RECEIPT:		5536.88

THANK YOU!!

G.S.T. REGISTRATION NUMBER R101565356

TERMS: NET 30 DAYS. INTEREST AT RATE OF 1 1/2 PER MONTH (18% PER ANNUM)
WILL BE CHARGED ON OVERDUE ACCOUNTS.

CERTIFICATE OF ANALYSIS AK 2002-326

BRIGHT STAR VENTURES
 Suite 205 - 555 Burrard Street
Po Box 218
 Vancouver, BC, V7X 1M7

25-Sep-02

ATTENTION: Bill Yeomans

No. of samples received: 251

Sample Type: Soil

Project #: Tulameen

Shipment #: 2-3

Samples submitted by: Bright Star Ventures

ET #.	Tag #		Au (ppb)	Pd (ppb)	Pt (ppb)
1	R5350N 9900	E	<5	<5	5
2	R5350N 9950	E	<5	<5	<5
3	R5350N 10000	E	<5	<5	<5
4	R5350N 10050	E	5	<5	5
5	R5350N 10100	E	<5	<5	5
6	R5350N 10150	E	<5	20	5
7	5650N 7800	E	<5	5	<5
8	5650N 7850	E	<5	<5	10
9	5650N 7900	E	<5	<5	5
10	5650N 7950	E	<5	<5	<5
11	5650N 8000	E	<5	<5	<5
12	5650N 8050	E	<5	<5	5
13	5650N 8100	E	<5	<5	<5
14	5650N 8150	E	5	5	5
15	5650N 8200	E	<5	<5	10
16	5650N 8250	E	<5	5	5
17	5650N 8300	E	<5	<5	10
18	5650N 8350	E	<5	<5	15
19	5650N 8400	E	<5	<5	15
20	5650N 8450	E	<5	<5	5
21	5650N 8500	E	5	5	5
22	5650N 8550	E	5	<5	20
23	5650N 8600	E	<5	<5	5
24	5650N 8650	E	5	5	<5
25	5650N 8700	E	No Sample		
26	5650N 8750	E	<5	<5	15
27	5650N 8800	E	<5	5	10
28	5650N 8850	E	<5	<5	10

25-Sep-02

ET #.	Tag #			Au (ppb)	Pd (ppb)	Pt (ppb)
29	5650N	8900	E	<5	<5	10
30	5650N	8950	E	<5	<5	10
31	5650N	9000	E	10	5	<5
32	5650N	9050	E	<5	<5	5
33	5650N	9100	E Swamp	No Sample		
34	5650N	9150	E	5	10	5
35	5650N	9200	E	5	5	10
36	5650N	9250	E	<5	<5	10
37	R5650N	9900	E	<5	5	10
38	R5650N	9950	E	5	5	5
39	R5650N	10000	E	5	5	5
40	R5650N	10050	E	<5	5	5
41	R5650N	10100	E	5	5	5
42	R5650N	10150	E	<5	5	10
43	R5800N	9900	E	5	15	5
44	R5800N	9950	E	<5	<5	<5
45	R5800N	10000	E	<5	5	10
46	R5800N	10050	E	<5	<5	<5
47	R5800N	10100	E	<5	<5	5
48	R5800N	10150	E	5	<5	10
49	5950N	7850	E	<5	<5	10
50	5950N	7900	E	<5	<5	<5
51	5950N	7950	E	<5	<5	<5
52	5950N	8000	E	<5	<5	10
53	5950N	8050	E	<5	<5	<5
54	5950N	8100	E	<5	<5	<5
55	5950N	8150	E	<5	5	15
56	5950N	8200	E	<5	5	10
57	5950N	8250	E	5	<5	20
58	5950N	8300	E	<5	5	15
59	5950N	8350	E	<5	<5	10
60	5950N	8400	E	<5	5	10
61	5950N	8450	E	<5	15	15
62	5950N	8500	E	<5	10	15
63	5950N	8550	E	5	20	10
64	5950N	8600	E	5	15	<5
65	5950N	8650	E	<5	<5	15
66	5950N	8700	E	<5	10	<5
67	5950N	8750	E	<5	10	20
68	5950N	8800	E	<5	5	25
69	5950N	8850	E Swamp	No Sample		
70	5950N	8900	E	<5	<5	5
71	5950N	8950	E	5	5	<5
72	5950N	9000	E	<5	5	10
73	5950N	9050	E	60	5	20
74	5950N	9100	E	5	<5	<5
75	5950N	9150	E	<5	5	5
76	5950N	9200	E	5	<5	10
77	5950N	9250	E	<5	15	10

BRIGHT STAR VENTURES AK2-2002-326

25-Sep-02

ET #.	Tag #		Au (ppb)	Pd (ppb)	Pt (ppb)
78	5950N 9300	E	<5	15	10
79	5950N 9350	E	<5	<5	10
80	5950N 9400	E	<5	<5	5
81	R5950N 9950	E	5	<5	<5
82	R5950N 10000	E	<5	10	<5
83	R5950N 10050	E	<5	<5	5
84	R5950N 10100	E	<5	5	<5
85	R5950N 10150	E	5	<5	<5
86	R5950N 10200	E	<5	5	5
87	6250N 7750	E	<5	<5	<5
88	6250N 7800	E	<5	5	5
89	6250N 7850	E	<5	<5	5
90	6250N 7900	E	<5	<5	15
91	6250N 7950	E	<5	<5	<5
92	6250N 8000	E	<5	<5	<5
93	6250N 8050	E	<5	<5	10
94	6250N 8100	E	5	<5	<5
95	6250N 8150	E	10	10	5
96	6250N 8200	E	<5	<5	10
97	6250N 8250	E	5	<5	<5
98	6250N 8300	E	5	<5	5
99	6250N 8350	E	5	<5	15
100	6250N 8400	E	5	<5	10
101	6250N 8450	E	<5	<5	15
102	6250N 8500	E	<5	<5	10
103	6250N 8550	E	<5	30	30
104	6250N 8600	E	5	<5	10
105	6250N 8650	E	<5	<5	15
106	6250N 8700	E	<5	<5	20
107	6250N 8750	E	<5	<5	25
108	6250N 8800	E	<5	<5	20
109	6250N 8850	E	<5	<5	10
110	6250N 8900	E	<5	<5	40
111	6550N 7650	E	<5	<5	5
112	6550N 7700	E	<5	5	15
113	6550N 7750	E	<5	<5	<5
114	6550N 7800	E	<5	<5	10
115	6550N 7850	E	<5	<5	10
116	6550N 7900	E	5	10	20
117	6550N 7950	E	<5	<5	10
118	6550N 8000	E	<5	<5	5
119	6550N 8050	E	<5	5	20
120	6550N 8100	E	<5	<5	<5
121	6550N 8150	E	<5	15	20
122	6550N 8200	E	<5	5	10
123	6550N 8250	E	20	<5	20
124	6550N 8300	E	<5	<5	10
125	6550N 8350	E	<5	5	5
126	6550N 8400	E	<5	<5	10

BRIGHT STAR VENTURES AK2-2002-326

25-Sep-02

ET #.	Tag #			Au (ppb)	Pd (ppb)	Pt (ppb)
127	6550N	8450	E	<5	5	5
128	6550N	8500	E	<5	<5	30
129	6550N	8550	E	<5	<5	10
130	6550N	8600	E	5	10	125
131	6550N	8650	E	<5	<5	10
132	6550N	8700	E	5	<5	20
133	6550N	8750	E	5	<5	10
134	6550N	8800	E	<5	<5	25
135	6550N	8850	E	<5	<5	10
136	6550N	8900	E	<5	<5	10
137	6550N	8950	E	<5	<5	10
138	6550N	9000	E	<5	<5	5
139	6550N	9050	E	<5	<5	<5
140	6550N	9100	E	<5	<5	<5
141	6550N	9150	E	<5	5	15
142	6550N	9200	E	<5	10	15
143	6550N	9250	E	5	5	5
144	6550N	9300	E	5	5	5
145	6550N	9350	E	<5	5	5
146	6550N	9400	E	10	<5	5
147	6550N	9450	E	5	<5	<5
148	6550N	9500	E	5	<5	10
149	6550N	9550	E	5	<5	<5
150	6550N	9600	E	5	5	<5
151	6550N	9650	E	<5	<5	5
152	6550N	9700	E	<5	5	10
153	6550N	9750	E	<5	5	5
154	6550N	9800	E	5	<5	10
155	6550N	9850	E	<5	<5	<5
156	6550N	9900	E	5	10	5
157	6550N	9950	E B/L	<5	<5	10
158	6850N	7650	E	<5	<5	<5
159	6850N	7700	E	<5	<5	15
160	6850N	7750	E	5	5	5
161	6850N	7800	E	<5	<5	<5
162	6850N	7850	E	5	<5	5
163	6850N	7900	E	<5	<5	<5
164	6850N	7950	E	<5	15	10
165	6850N	8000	E	<5	10	<5
166	6850N	8050	E	<5	<5	<5
167	6850N	8100	E	<5	<5	<5
168	6850N	8150	E	<5	<5	<5
169	6850N	8200	E	<5	<5	10
170	6850N	8250	E	<5	<5	<5
171	6850N	8300	E	<5	10	<5
172	6850N	8350	E	5	<5	<5
173	6850N	8400	E	5	10	50
174	6850N	8450	E	<5	15	10
175	6850N	8500	E	<5	45	15

BRIGHT STAR VENTURES AK2-2002-326

25-Sep-02

ET #.	Tag #		Au (ppb)	Pd (ppb)	Pt (ppb)
176	6850N 8550	E	<5	30	<5
177	6850N 8600	E	<5	5	95
178	6850N 8650	E	<5	<5	10
179	6850N 8700	E	<5	<5	<5
180	6850N 8750	E	<5	20	<5
181	6850N 8800	E	<5	5	<5
182	6850N 8850	E	<5	15	<5
183	6850N 8900	E	<5	15	<5
184	6850N 8950	E	<5	5	20
185	6850N 9000	E	<5	5	<5
186	6850N 9050	E	<5	10	10
187	6850N 9100	E	<5	<5	5
188	6850N 9150	E	<5	<5	<5
189	6850N 9200	E	<5	15	5
190	6850N 9250	E	<5	<5	10
191	6850N 9300	E Talus	No Sample		
192	6850N 9350	E	<5	25	<5
193	6850N 9400	E	110	5	5
194	6850N 9450	E	<5	<5	20
195	6850N 9500	E	<5	<5	10
196	6850N 9550	E	5	15	<5
197	6850N 9600	E	<5	<5	<5
198	6850N 9650	E	<5	<5	30
199	6850N 9700	E	<5	<5	10
200	6850N 9750	E	<5	<5	<5
201	6850N 9800	E	<5	10	<5
202	6850N 9850	E	<5	5	5
203	6850N 9900	E	<5	5	5
204	6850N 9950	E	<5	5	5
205	7150N 7650	E	<5	<5	40
206	7150N 7700	E	<5	5	5
207	7150N 7750	E	10	10	25
208	7150N 7800	E	<5	5	20
209	7150N 7850	E	<5	20	20
210	7150N 7900	E	<5	<5	30
211	7150N 7950	E	5	<5	15
212	7150N 8000	E	<5	15	10
213	7150N 8050	E	<5	45	<5
214	7150N 8100	E	<5	<5	<5
215	7150N 8150	E	<5	<5	35
216	7150N 8200	E	<5	<5	25
217	7150N 8250	E	<5	<5	15
218	7150N 8300	E	<5	<5	40
219	7150N 8350	E	5	<5	15
220	7150N 8400	E	<5	<5	35
221	7150N 8450	E	<5	<5	5
222	7150N 8500	E	<5	15	20
223	7150N 8550	E	<5	25	5
224	7150N 8600	E	<5	40	10

BRIGHT STAR VENTURES AK2-2002-326

25-Sep-02

ET #.	Tag #		Au (ppb)	Pd (ppb)	Pt (ppb)
225	7150N 8650	E	<5	10	10
226	7150N 8700	E	<5	<5	<5
227	7150N 8750	E	<5	5	5
228	7150N 8800	E	<5	<5	5
229	7150N 8850	E	<5	<5	5
230	7150N 8900	E	<5	15	<5
231	7150N 8950	E	<5	5	<5
232	7150N 9000	E	<5	<5	5
233	7150N 9050	E	<5	<5	<5
234	7150N 9100	E	<5	<5	5
235	7150N 9150	E	<5	<5	<5
236	7150N 9200	E	<5	5	5
237	7150N 9250	E	<5	5	<5
238	7150N 9300	E	20	5	25
239	7150N 9350	E	<5	5	<5
240	7150N 9400	E	<5	5	<5
241	7150N 9450	E	20	15	<5
242	7150N 9500	E	<5	5	<5
243	7150N 9550	E	<5	<5	<5
244	7150N 9600	E	<5	<5	<5
245	7150N 9650	E	<5	20	<5
246	7150N 9700	E	<5	10	5
247	7150N 9750	E	<5	<5	<5
248	7150N 9800	E	<5	5	<5
249	7150N 9850	E	<5	<5	5
250	7150N 9900	E	<5	20	5
251	7150N 9950	E	<5	<5	<5

QC DATA:

Repeat:

3	R5350N 10000	E	<5	<5	<5
12	5650N 8050	E	<5	<5	<5
22	5650N 8550	E	<5	<5	20
30	5650N 8950	E	5	5	10
41	R5650N 10100	E	<5	5	5
52	5950N 8000	E	<5	<5	<5
61	5950N 8450	E	<5	10	15
71	5950N 8950	E	<5	5	<5
82	R5950N 10000	E	<5	<5	5
90	6250N 7900	E	<5	<5	<5
101	6250N 8450	E	<5	<5	20
110	6250N 8900	E	<5	5	45
124	6550N 8300	E	<5	<5	10
134	6550N 8800	E	<5	<5	20
142	6550N 9200	E	<5	<5	15
146	6550N 9400	E	<5	5	<5
168	6850N 8150	E	<5	<5	20

ET #.	Tag #	Au (ppb)	Pd (ppb)	Pt (ppb)
-------	-------	-------------	-------------	-------------

QC DATA:

Repeat:

183	6850N 8900	E	<5	5	10
198	6850N 9650	E	<5	<5	10
203	6850N 9900	E	<5	5	<5
214	7150N 8100	E	<5	5	<5
221	7150N 8450	E	<5	<5	5
231	7150N 8950	E	<5	<5	5
243	7150N 9550	E	<5	<5	5

Standard:

PG101			70	540	270
PG101			70	540	270
PG101			70	530	280
PG101			70	550	270
PG101			60	520	270
PG101			70	530	270
PG101			75	540	270
PG101			70	560	260
PG101			70	560	250
PG101			70	560	260
PG101			70	540	270
PG101			70	520	250

JJ/kk
XLS/02

ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

September 24, 2002

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2002-326

BRIGHT STAR VENTURES
Suite 205 - 555 Burrard Street
Po Box 218
Vancouver, BC, V7X 1M7

ATTENTION: Bill Yeomans

No. of samples received: 251

Sample Type: Soil

Project #: Tulameen

Shipment #: 2-3

Samples submitted by: Brightstar Ventures

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	R5350N 9900 E	<0.2	2.58	<5	65	5	0.41	<1	23	39	96	3.97	10	1.12	395	<1	0.02	23	1530	14	<5	<20	28	0.10	<10	122	<10	6	65
2	R5350N 9950 E	<0.2	2.40	<5	60	5	0.31	<1	22	38	83	4.11	10	0.97	393	<1	0.02	20	1400	16	<5	<20	29	0.10	<10	138	<10	7	66
3	R5350N 10000 E	<0.2	2.24	<5	50	10	0.49	<1	27	33	111	4.21	10	1.27	522	<1	0.02	18	2240	12	<5	<20	42	0.12	<10	148	<10	7	69
4	R5350N 10050 E	<0.2	2.56	<5	115	10	0.69	<1	44	150	103	6.87	20	2.17	779	<1	0.02	68	2790	8	<5	<20	51	0.13	10	222	<10	7	80
5	R5350N 10100 E	<0.2	2.72	<5	110	5	0.52	<1	37	56	117	6.44	10	1.70	491	<1	0.02	28	2660	12	<5	<20	37	0.15	10	212	<10	8	86
6	R5350N 10150 E	<0.2	3.47	<5	85	10	1.70	<1	47	60	165	6.73	20	2.80	1040	<1	0.04	40	3040	16	<5	<20	35	0.16	<10	244	<10	13	117
7	5650N 7800 E	<0.2	1.58	35	85	<5	1.20	<1	12	70	45	1.91	<10	0.61	184	<1	0.03	43	700	10	<5	<20	29	0.04	<10	52	<10	7	25
8	5650N 7850 E	<0.2	2.40	45	145	10	0.61	<1	25	127	33	4.71	10	1.18	522	<1	0.02	54	380	12	<5	<20	24	0.10	<10	122	<10	7	57
9	5650N 7900 E	<0.2	2.58	<5	75	10	0.20	<1	27	152	45	4.49	<10	1.36	263	<1	0.02	78	620	14	<5	<20	10	0.10	<10	109	<10	6	67
10	5650N 7950 E	<0.2	2.88	<5	40	10	0.23	<1	29	181	48	4.10	10	1.76	337	<1	0.02	80	620	16	<5	<20	11	0.13	10	93	<10	7	54
11	5650N 8000 E	<0.2	2.27	<5	60	10	0.28	<1	23	101	27	3.51	10	1.26	358	<1	0.02	61	1050	14	<5	<20	10	0.11	<10	59	<10	5	68
12	5650N 8050 E	<0.2	2.44	<5	55	15	0.34	<1	27	91	30	3.23	<10	1.61	613	<1	0.02	71	1080	14	<5	<20	20	0.19	<10	52	<10	7	72
13	5650N 8100 E	<0.2	2.40	10	95	10	0.22	<1	24	105	42	4.12	<10	1.20	566	<1	0.02	53	950	8	<5	<20	13	0.09	<10	89	<10	5	83
14	5650N 8150 E	<0.2	3.63	30	835	<5	0.98	<1	52	45	223	6.67	10	3.40	2053	<1	0.02	24	2910	6	<5	<20	37	0.16	10	223	<10	7	124
15	5650N 8200 E	<0.2	1.82	<5	115	10	0.28	<1	19	55	29	4.26	<10	0.99	343	<1	0.02	20	530	8	<5	<20	21	0.12	<10	139	<10	6	51
16	5650N 8250 E	<0.2	1.85	<5	55	10	0.39	<1	32	47	8	5.90	<10	1.29	551	<1	0.04	26	540	6	<5	<20	9	0.14	10	243	<10	6	58
17	5650N 8300 E	<0.2	2.55	<5	90	5	0.37	<1	31	139	33	5.65	<10	1.37	274	<1	0.02	54	450	8	<5	<20	21	0.12	<10	184	<10	7	47
18	5650N 8350 E	<0.2	1.43	<5	50	10	0.19	<1	19	160	6	4.61	<10	0.54	117	<1	0.02	30	470	6	<5	<20	5	0.12	<10	150	<10	5	34
19	5650N 8400 E	<0.2	2.24	120	90	10	0.42	<1	44	122	14	8.93	10	1.42	418	<1	0.03	62	360	4	<5	<20	9	0.14	10	302	<10	6	61
20	5650N 8450 E	<0.2	2.16	<5	130	10	0.46	<1	27	158	21	5.65	<10	1.01	290	<1	0.02	58	190	6	<5	<20	10	0.11	<10	218	<10	8	33
21	5650N 8500 E	<0.2	1.32	<5	95	5	0.28	<1	17	178	14	4.73	<10	0.57	216	<1	0.02	32	160	6	<5	<20	13	0.11	<10	142	<10	5	32
22	5650N 8550 E	<0.2	1.59	<5	55	10	0.34	<1	23	147	23	4.15	<10	0.98	253	<1	0.02	53	860	6	<5	<20	28	0.09	<10	111	<10	5	50
23	5650N 8600 E	<0.2	3.04	<5	55	10	0.42	<1	28	78	26	4.88	<10	1.15	364	<1	0.04	38	1010	12	<5	<20	20	0.14	<10	98	<10	7	67
24	5650N 8650 E	<0.2	1.78	<5	35	5	0.31	<1	16	84	20	3.66	<10	0.61	164	<1	0.02	25	1230	8	<5	<20	21	0.09	<10	97	<10	4	43
25	5650N 8700 E	No Sample																											

BRIGHT STAR VENTURES

ICP CERTIFICATE OF ANALYSIS AK 2002-326

ECO TECH LABORATORY LTD.

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	5650N 8750 E	<0.2	1.91	<5	50	5	0.36	<1	20	96	41	4.28	<10	0.83	212	<1	0.02	28	1240	8	<5	<20	35	0.09	10	122	<10	5	39
27	5650N 8800 E	<0.2	2.40	<5	60	10	0.34	<1	23	107	47	4.54	<10	0.93	248	<1	0.02	34	1340	10	<5	<20	31	0.10	<10	125	<10	7	51
28	5650N 8850 E	<0.2	2.18	<5	85	10	0.40	2	23	94	44	4.18	<10	0.96	314	<1	0.02	39	1090	10	<5	<20	34	0.10	<10	114	<10	6	55
29	5650N 8900 E	<0.2	1.94	<5	85	10	0.32	<1	19	92	41	3.93	<10	0.76	181	<1	0.02	31	1020	10	<5	<20	32	0.09	<10	110	<10	6	42
30	5650N 8950 E	<0.2	1.92	<5	85	5	0.44	<1	20	77	51	3.85	<10	0.98	288	<1	0.02	34	940	8	<5	<20	38	0.09	10	106	<10	5	47
31	5650N 9000 E	<0.2	2.40	<5	105	<5	0.50	<1	23	84	87	4.26	<10	1.11	331	<1	0.02	38	1480	10	<5	<20	42	0.09	<10	120	<10	6	58
32	5650N 9050 E	<0.2	2.08	<5	120	<5	0.55	1	21	75	64	3.54	10	0.96	288	<1	0.03	34	990	10	<5	<20	45	0.08	<10	102	<10	9	43
33	5650N 9100 E Swamp	No Sample																											
34	5650N 9150 E	<0.2	2.15	<5	55	<5	0.56	<1	25	71	90	4.88	10	1.38	326	<1	0.02	28	2120	6	<5	<20	49	0.10	<10	167	<10	6	51
35	5650N 9200 E	<0.2	2.47	15	130	<5	0.57	<1	29	223	86	4.77	10	1.50	693	<1	0.03	95	1100	10	<5	<20	51	0.09	10	148	<10	10	50
36	5650N 9250 E	<0.2	2.17	<5	70	5	0.42	<1	24	118	53	4.85	10	1.22	271	<1	0.02	40	1440	6	<5	<20	41	0.10	<10	140	<10	6	52
37	R5650N 9900 E	<0.2	2.39	<5	80	10	0.65	<1	30	68	61	4.68	10	1.56	659	<1	0.02	33	2680	8	<5	<20	64	0.12	<10	170	<10	7	93
38	R5650N 9950 E	<0.2	2.47	<5	75	5	0.58	9	30	74	95	4.76	10	1.57	654	<1	0.02	44	2370	10	<5	<20	50	0.11	<10	161	<10	6	95
39	R5650N 10000 E	<0.2	2.66	<5	85	10	0.53	<1	29	61	145	4.63	10	1.48	494	<1	0.02	30	1990	12	<5	<20	37	0.12	<10	155	<10	7	81
40	R5650N 10050 E	<0.2	2.73	<5	115	<5	1.33	<1	48	39	407	7.21	30	2.85	1051	<1	0.02	29	4630	6	<5	<20	68	0.14	<10	333	<10	14	121
41	R5650N 10100 E	<0.2	2.75	<5	80	<5	0.75	8	38	97	157	5.90	20	1.90	1258	<1	0.03	62	2750	10	<5	<20	55	0.14	10	208	<10	8	116
42	R5650N 10150 E	<0.2	2.30	<5	40	5	0.63	<1	28	45	123	4.50	<10	1.61	621	<1	0.02	25	2160	8	<5	<20	63	0.12	<10	157	<10	6	68
43	R5800N 9900 E	<0.2	3.06	<5	100	<5	0.67	<1	33	49	276	4.85	10	1.83	1135	<1	0.02	31	2030	14	<5	<20	71	0.14	<10	188	<10	9	96
44	R5800N 9950 E	<0.2	2.86	<5	200	5	0.69	<1	27	35	160	4.26	20	1.49	771	<1	0.02	24	1180	14	<5	<20	89	0.12	<10	161	<10	13	87
45	R5800N 10000 E	<0.2	2.83	<5	40	5	0.92	<1	42	27	86	4.36	20	2.72	973	<1	0.02	26	2980	12	<5	<20	51	0.12	<10	181	<10	9	115
46	R5800N 10050 E	<0.2	2.81	<5	50	<5	0.93	<1	31	36	205	5.02	10	1.61	673	<1	0.02	23	2060	12	<5	<20	37	0.12	<10	176	<10	9	95
47	R5800N 10100 E	<0.2	3.01	<5	40	<5	1.02	<1	40	40	265	6.00	20	2.42	1040	<1	0.02	27	3110	10	<5	<20	52	0.16	10	224	<10	11	110
48	R5800N 10150 E	<0.2	2.71	<5	75	<5	0.39	<1	31	52	177	4.66	<10	1.25	550	<1	0.03	27	1590	10	<5	<20	20	0.11	<10	140	<10	7	68
49	5950N 7850 E	<0.2	2.28	30	90	<5	0.18	<1	20	105	32	3.80	<10	1.03	312	<1	0.02	53	1050	10	<5	<20	9	0.06	<10	84	<10	3	55
50	5950N 7900 E	<0.2	1.98	15	60	5	0.21	<1	19	88	29	3.76	<10	1.08	269	<1	0.02	34	900	8	<5	<20	11	0.07	<10	92	<10	4	53
51	5950N 7950 E	<0.2	2.46	<5	90	10	0.21	<1	23	84	59	4.05	<10	1.50	407	<1	0.02	37	590	8	<5	<20	12	0.09	10	102	<10	5	54
52	5950N 8000 E	<0.2	2.60	30	95	<5	0.21	<1	22	89	42	4.15	<10	1.29	539	<1	0.02	42	940	10	<5	<20	13	0.07	<10	92	<10	4	65
53	5950N 8050 E	<0.2	2.14	<5	115	5	0.29	<1	21	64	42	3.92	<10	0.97	715	<1	0.02	30	970	10	<5	<20	19	0.09	10	106	<10	5	76
54	5950N 8100 E	<0.2	2.56	<5	235	<5	0.39	<1	26	50	81	4.41	<10	1.88	814	<1	0.02	20	1850	10	<5	<20	18	0.10	10	131	<10	5	88
55	5950N 8150 E	<0.2	1.66	<5	90	5	0.23	<1	23	106	38	4.32	<10	1.07	777	<1	0.02	33	770	6	<5	<20	12	0.08	<10	128	<10	4	47
56	5950N 8200 E	<0.2	1.66	<5	145	5	0.23	<1	23	97	35	4.11	<10	0.93	590	<1	0.02	26	890	8	<5	<20	20	0.10	10	116	<10	5	53
57	5950N 8250 E	<0.2	2.15	<5	65	10	0.20	<1	29	126	36	5.66	<10	1.26	382	<1	0.02	37	430	8	<5	<20	15	0.13	10	193	<10	6	52
58	5950N 8300 E	<0.2	1.90	<5	85	10	0.28	<1	28	114	29	5.83	<10	1.33	533	<1	0.02	39	440	6	<5	<20	21	0.14	10	195	<10	6	48
59	5950N 8350 E	<0.2	1.97	<5	65	10	0.20	<1	24	133	26	5.12	<10	0.88	265	<1	0.02	37	420	10	<5	<20	16	0.11	<10	149	<10	6	43
60	5950N 8400 E	<0.2	1.88	<5	40	10	0.26	<1	31	104	21	7.13	10	1.06	300	<1	0.02	35	360	6	<5	<20	18	0.14	<10	250	<10	7	60

BRIGHT STAR VENTURES

ICP CERTIFICATE OF ANALYSIS AK 2002-326

ECO TECH LABORATORY LTD.

Et #	Tag #	Ag	Al %	As	Ba	Bl	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
61	5950N 8450 E	<0.2	2.63	<5	55	10	0.31	<1	37	115	32	7.44	10	1.32	232	<1	0.03	45	330	8	<5	<20	13	0.15	10	265	<10	7	62
62	5950N 8500 E	<0.2	2.01	<5	55	15	0.42	<1	35	153	25	8.18	10	1.30	244	<1	0.02	46	280	6	<5	<20	13	0.17	10	292	<10	7	58
63	5950N 8550 E	<0.2	1.41	<5	50	10	0.25	<1	24	103	16	6.02	<10	1.00	169	<1	0.03	29	490	6	<5	<20	7	0.17	<10	229	<10	8	46
64	5950N 8600 E	<0.2	2.36	<5	230	<5	0.55	<1	28	132	87	5.38	10	1.16	733	<1	0.03	66	240	10	<5	<20	23	0.12	<10	205	<10	11	50
65	5950N 8650 E	<0.2	1.69	<5	100	5	0.32	<1	30	228	25	5.47	<10	1.04	316	<1	0.03	64	710	6	<5	<20	12	0.11	10	160	<10	5	57
66	5950N 8700 E	<0.2	1.55	<5	145	<5	0.58	<1	21	109	44	4.57	10	0.87	302	<1	0.02	39	670	4	<5	<20	31	0.09	<10	134	<10	6	43
67	5950N 8750 E	<0.2	2.08	<5	95	10	0.33	<1	25	153	29	4.52	<10	1.05	237	<1	0.02	48	660	10	<5	<20	18	0.11	10	125	<10	6	51
68	5950N 8800 E	<0.2	1.66	<5	45	10	0.28	<1	38	667	11	9.10	10	1.92	4	<1	0.02	98	130	<2	<5	<20	2	0.14	10	214	<10	5	51
69	5950N 8850 E	Swamp		No Sample																									
70	5950N 8900 E	<0.2	2.18	<5	70	10	0.39	<1	19	61	47	4.33	10	0.91	236	<1	0.02	21	1550	8	<5	<20	33	0.09	<10	127	<10	6	53
71	5950N 8950 E	<0.2	3.16	<5	215	5	1.32	<1	24	66	94	4.33	20	1.14	868	<1	0.04	35	760	12	<5	<20	92	0.12	<10	148	<10	17	49
72	5950N 9000 E	<0.2	3.03	<5	165	5	0.89	<1	27	79	101	4.93	10	1.20	383	<1	0.03	35	1410	14	<5	<20	115	0.14	<10	161	<10	10	70
73	5950N 9050 E	<0.2	2.93	<5	220	10	1.33	<1	27	74	121	4.55	20	1.47	693	<1	0.04	39	980	12	<5	<20	120	0.14	<10	154	<10	14	65
74	5950N 9100 E	<0.2	3.10	<5	235	10	1.15	<1	26	76	129	4.82	20	1.19	1234	<1	0.05	41	770	16	<5	<20	92	0.14	<10	155	<10	13	73
75	5950N 9150 E	<0.2	3.76	<5	270	10	1.04	<1	24	75	138	4.61	20	1.21	814	<1	0.05	43	960	18	<5	<20	73	0.13	<10	141	<10	18	75
76	5950N 9200 E	<0.2	3.40	<5	160	10	0.75	<1	21	65	104	3.14	20	1.09	305	<1	0.05	42	800	20	<5	<20	74	0.14	<10	103	<10	17	51
77	5950N 9250 E	<0.2	2.61	<5	160	10	1.06	<1	32	99	71	5.14	10	1.58	395	<1	0.04	46	800	12	<5	<20	147	0.18	<10	171	<10	11	65
78	5950N 9300 E	<0.2	2.25	<5	110	15	0.71	<1	23	79	46	3.98	10	1.00	232	<1	0.03	27	240	12	<5	<20	145	0.19	<10	175	<10	12	34
79	5950N 9350 E	<0.2	2.70	<5	80	15	0.62	<1	33	139	52	5.50	10	1.46	365	<1	0.03	48	1580	10	<5	<20	136	0.16	10	169	<10	9	64
80	5950N 9400 E	<0.2	2.39	<5	100	10	0.83	<1	26	122	56	4.72	10	1.35	384	<1	0.04	36	1880	10	<5	<20	148	0.14	<10	148	<10	8	59
81	R5950N 9950 E	<0.2	3.26	<5	95	5	0.86	<1	34	54	169	5.61	20	2.06	675	<1	0.03	33	2500	12	<5	<20	86	0.13	10	212	<10	10	90
82	R5950N 10000 E	<0.2	3.13	<5	100	10	0.82	<1	34	69	122	5.46	20	2.02	498	<1	0.03	41	1520	12	<5	<20	111	0.17	10	191	<10	10	76
83	R5950N 10050 E	<0.2	3.30	<5	80	10	0.54	<1	29	54	108	5.21	10	1.55	464	<1	0.04	28	1890	14	<5	<20	56	0.14	10	172	<10	9	69
84	R5950N 10100 E	<0.2	3.50	<5	90	10	1.15	<1	43	109	228	6.58	20	3.10	935	<1	0.03	57	2420	12	<5	<20	167	0.20	10	262	<10	13	103
85	R5950N 10150 E	<0.2	2.98	<5	55	10	0.73	<1	27	51	88	5.00	10	1.54	549	<1	0.07	23	2190	12	<5	<20	56	0.16	<10	172	<10	11	65
86	R5950N 10200 E	<0.2	2.91	<5	80	10	0.66	<1	26	39	85	4.44	10	1.37	451	<1	0.05	20	1470	14	<5	<20	65	0.16	<10	151	<10	10	69
87	6250N 7750 E	<0.2	2.63	35	150	5	0.56	<1	27	71	101	5.38	20	1.23	623	<1	0.03	41	820	12	<5	<20	48	0.09	<10	113	<10	9	62
88	6250N 7800 E	<0.2	3.36	20	160	10	1.46	<1	28	65	67	4.92	10	1.06	1131	<1	0.04	31	1230	14	<5	<20	47	0.13	10	111	<10	11	126
89	6250N 7850 E	<0.2	3.01	<5	135	5	0.51	<1	23	49	43	4.94	10	1.68	1322	<1	0.03	22	980	12	<5	<20	25	0.10	10	149	<10	5	79
90	6250N 7900 E	<0.2	2.95	<5	80	15	0.51	<1	27	126	49	4.13	10	1.56	413	<1	0.03	71	1010	14	<5	<20	26	0.13	<10	97	<10	8	71
91	6250N 7950 E	<0.2	2.32	10	90	5	0.34	<1	21	80	58	4.44	10	0.89	496	<1	0.03	31	920	10	<5	<20	25	0.12	10	117	<10	8	83
92	6250N 8000 E	<0.2	2.84	<5	115	10	0.40	<1	34	72	141	5.48	10	1.68	912	<1	0.04	31	990	12	<5	<20	27	0.25	<10	193	<10	10	80
93	6250N 8050 E	<0.2	3.76	<5	90	10	0.54	1	49	76	223	9.72	20	2.65	831	<1	0.04	32	1280	8	<5	<20	28	0.22	10	429	<10	13	76
94	6250N 8100 E	<0.2	2.71	<5	130	<5	1.08	<1	24	138	78	4.05	10	1.13	914	<1	0.04	36	890	12	<5	<20	75	0.09	<10	131	<10	10	49
95	6250N 8150 E	<0.2	2.78	<5	75	5	0.64	<1	25	87	69	5.01	10	1.39	421	<1	0.04	32	650	10	<5	<20	68	0.14	<10	170	<10	9	56

BRIGHT STAR VENTURES

ICP CERTIFICATE OF ANALYSIS AK 2002-326

ECO TECH LABORATORY LTD.

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
96	6250N 8200	E	<0.2	2.79	<5	140	<5	1.42	<1	24	102	82	4.12	20	1.18	1222	<1	0.05	32	1000	12	<5	<20	83	0.09	<10	138	<10	12	53
97	6250N 8250	E	<0.2	3.03	<5	225	5	1.29	<1	26	83	86	4.48	20	1.23	1212	<1	0.04	38	940	14	<5	<20	65	0.11	<10	171	<10	13	64
98	6250N 8300	E	<0.2	2.31	<5	115	15	0.75	<1	29	57	61	5.19	10	1.19	472	<1	0.04	29	560	10	<5	<20	62	0.18	<10	214	<10	12	63
99	6250N 8350	E	<0.2	1.19	<5	40	15	0.32	<1	20	121	13	5.23	<10	0.67	116	<1	0.03	27	540	6	<5	<20	27	0.16	<10	187	<10	7	37
100	6250N 8400	E	<0.2	1.49	<5	55	10	0.33	<1	24	163	21	6.17	10	0.83	161	<1	0.03	40	260	4	<5	<20	25	0.18	10	221	<10	9	39
101	6250N 8450	E	<0.2	1.43	<5	50	15	0.44	<1	20	83	16	4.37	10	0.72	181	<1	0.03	27	360	10	<5	<20	51	0.18	<10	157	<10	10	37
102	6250N 8500	E	<0.2	2.05	<5	55	10	0.48	<1	19	109	26	4.48	<10	0.98	197	<1	0.04	30	390	10	<5	<20	58	0.15	10	157	<10	8	42
103	6250N 8550	E	<0.2	1.48	<5	70	15	0.42	<1	27	73	24	6.97	10	0.88	139	<1	0.07	30	300	4	<5	<20	20	0.22	10	321	<10	10	48
104	6250N 8600	E	<0.2	1.35	<5	25	10	0.25	<1	10	78	11	3.02	<10	0.35	92	<1	0.03	15	350	10	<5	<20	32	0.12	<10	91	<10	6	28
105	6250N 8650	E	<0.2	1.70	<5	45	10	0.30	<1	15	202	19	3.71	<10	0.66	163	<1	0.03	27	600	10	<5	<20	36	0.12	<10	101	<10	6	36
106	6250N 8700	E	<0.2	1.76	15	65	10	0.37	<1	21	302	30	3.54	<10	0.96	388	<1	0.03	52	470	8	<5	<20	41	0.10	<10	94	<10	6	58
107	6250N 8750	E	<0.2	1.64	<5	30	15	0.27	<1	20	199	19	4.77	<10	0.74	116	<1	0.03	33	310	6	<5	<20	27	0.14	<10	127	<10	8	32
108	6250N 8800	E	<0.2	1.14	<5	5	10	0.21	<1	22	72	7	6.42	10	0.54	38	<1	0.03	25	490	2	<5	<20	3	0.15	<10	156	<10	7	31
109	6250N 8850	E	<0.2	2.14	<5	55	10	0.44	<1	22	124	32	4.31	<10	0.97	219	<1	0.03	39	560	10	<5	<20	40	0.14	<10	127	<10	7	44
110	6250N 8900	E	<0.2	1.34	<5	25	10	0.17	<1	17	680	11	3.19	<10	1.18	111	<1	0.02	46	260	4	<5	<20	3	0.09	<10	77	<10	4	29
111	6550N 7650	E	<0.2	3.21	<5	70	10	0.31	<1	28	203	61	4.21	<10	2.08	353	<1	0.02	82	750	12	<5	<20	24	0.11	10	108	<10	6	56
112	6550N 7700	E	<0.2	3.48	<5	115	10	0.36	<1	29	182	53	4.99	10	2.14	494	<1	0.02	96	800	14	<5	<20	14	0.12	<10	112	<10	8	65
113	6550N 7750	E	<0.2	2.75	10	95	10	0.34	<1	23	137	46	4.55	10	1.41	401	<1	0.03	61	930	12	<5	<20	20	0.09	10	113	<10	6	80
114	6550N 7800	E	<0.2	3.24	<5	55	15	0.41	<1	30	172	38	3.95	<10	2.11	432	<1	0.02	99	1210	14	<5	<20	21	0.18	<10	94	<10	9	65
115	6550N 7850	E	0.4	2.03	<5	70	10	0.29	<1	23	72	41	4.24	<10	1.02	1366	<1	0.03	31	840	10	<5	<20	20	0.11	10	110	<10	6	62
116	6550N 7900	E	<0.2	2.44	<5	160	10	0.58	<1	36	55	114	5.62	10	1.86	1127	<1	0.04	25	940	6	<5	<20	30	0.16	10	202	<10	9	77
117	6550N 7950	E	<0.2	4.01	<5	185	10	0.41	<1	47	57	254	7.19	10	2.97	1056	<1	0.03	26	780	12	<5	<20	24	0.20	10	270	<10	12	98
118	6550N 8000	E	<0.2	2.64	<5	50	<5	0.26	<1	27	122	112	6.14	10	1.28	571	<1	0.03	35	900	8	<5	<20	19	0.14	10	209	<10	7	61
119	6550N 8050	E	<0.2	2.22	<5	155	<5	0.54	<1	24	85	179	4.20	<10	1.12	866	<1	0.03	27	1970	8	<5	<20	26	0.10	10	134	<10	6	50
120	6550N 8100	E	<0.2	2.31	<5	110	<5	0.92	<1	19	107	57	3.41	10	0.87	908	<1	0.03	27	830	12	<5	<20	53	0.08	<10	112	<10	9	48
121	6550N 8150	E	<0.2	2.36	<5	70	15	0.69	<1	31	84	43	6.51	10	1.48	429	<1	0.05	31	480	8	<5	<20	52	0.18	10	239	<10	10	59
122	6550N 8200	E	<0.2	2.78	<5	110	10	0.81	<1	35	67	65	5.40	10	1.95	765	<1	0.04	43	590	10	<5	<20	49	0.14	<10	214	<10	13	48
123	6550N 8250	E	<0.2	2.82	<5	150	10	0.75	<1	35	131	62	6.21	10	1.74	1008	<1	0.04	46	680	10	<5	<20	58	0.15	<10	207	<10	10	64
124	6550N 8300	E	<0.2	2.85	<5	70	10	0.45	<1	25	117	43	5.25	10	1.25	408	<1	0.04	35	830	12	<5	<20	41	0.14	<10	170	<10	9	68
125	6550N 8350	E	<0.2	3.00	<5	275	5	0.77	<1	26	84	69	4.62	10	1.23	624	<1	0.04	43	390	14	<5	<20	50	0.14	<10	177	<10	11	59
126	6550N 8400	E	<0.2	2.98	<5	145	10	0.66	<1	33	107	92	5.40	10	1.69	561	<1	0.04	45	670	12	<5	<20	59	0.14	<10	186	<10	10	74
127	6550N 8450	E	<0.2	2.67	<5	160	10	0.59	<1	33	115	70	5.35	10	1.32	397	<1	0.03	45	590	12	<5	<20	39	0.14	<10	179	<10	9	51
128	6550N 8500	E	<0.2	2.52	<5	110	15	0.59	<1	34	94	76	5.36	10	1.40	406	<1	0.03	44	400	10	<5	<20	51	0.17	<10	221	<10	10	63
129	6550N 8550	E	<0.2	1.95	40	135	10	0.54	<1	28	183	42	3.74	10	0.99	425	<1	0.03	129	390	10	<5	<20	39	0.11	<10	112	<10	9	44
130	6550N 8600	E	<0.2	1.84	10	85	15	0.56	<1	23	126	47	4.26	<10	1.02	301	<1	0.03	57	600	8	<5	<20	56	0.12	<10	137	<10	8	43

BRIGHT STAR VENTURES

ICP CERTIFICATE OF ANALYSIS AK 2002-326

ECO TECH LABORATORY LTD.

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
131	6550N 8650	E	<0.2	3.75	30	110	15	0.58	<1	41	191	51	5.20	10	1.66	331	<1	0.03	118	690	16	<5	<20	48	0.14	<10	144	<10	8	68
132	6550N 8700	E	<0.2	1.56	<5	50	5	0.31	<1	77	183	29	4.34	<10	1.95	577	<1	0.03	145	560	6	<5	<20	29	0.12	<10	71	<10	5	54
133	6550N 8750	E	<0.2	1.27	<5	40	10	0.28	<1	21	330	10	2.72	<10	1.30	245	<1	0.02	60	580	8	<5	<20	16	0.09	10	68	<10	4	49
134	6550N 8800	E	<0.2	2.25	<5	50	10	0.63	<1	40	142	30	4.17	10	1.97	477	<1	0.03	94	860	10	<5	<20	65	0.16	<10	130	<10	9	76
135	6550N 8850	E	<0.2	0.78	<5	25	10	0.42	<1	11	29	4	1.82	<10	0.41	120	<1	0.02	8	250	6	<5	<20	70	0.13	<10	82	<10	7	23
136	6550N 8900	E	<0.2	2.35	<5	105	10	0.72	<1	26	238	61	4.16	10	1.52	420	<1	0.03	80	550	10	<5	<20	63	0.11	<10	141	<10	8	51
137	6550N 8950	E	<0.2	3.08	40	265	10	1.35	<1	26	217	108	4.29	20	1.55	1272	<1	0.04	108	440	12	<5	<20	77	0.12	<10	151	<10	15	54
138	6550N 9000	E	<0.2	2.05	<5	80	10	0.63	<1	20	47	57	3.63	<10	0.98	232	<1	0.03	22	600	10	<5	<20	70	0.13	<10	131	<10	8	45
139	6550N 9050	E	<0.2	2.09	<5	65	10	0.54	<1	20	51	57	4.03	<10	0.99	231	<1	0.03	20	990	10	<5	<20	77	0.13	<10	150	<10	8	45
140	6550N 9100	E	<0.2	2.15	<5	65	10	0.49	<1	19	45	65	3.73	<10	0.98	213	<1	0.03	19	1180	10	<5	<20	79	0.13	<10	143	<10	8	42
141	6550N 9150	E	<0.2	2.00	30	220	<5	1.18	<1	32	150	72	7.17	20	1.42	2065	<1	0.04	57	1200	2	<5	<20	72	0.12	<10	188	<10	13	46
142	6550N 9200	E	<0.2	2.07	<5	50	5	0.57	<1	23	58	72	4.15	10	1.17	356	<1	0.02	23	1720	8	<5	<20	75	0.12	<10	149	<10	7	48
143	6550N 9250	E	<0.2	2.29	<5	65	10	0.69	<1	26	43	111	3.80	<10	1.39	360	<1	0.02	22	2160	10	<5	<20	85	0.12	<10	148	<10	8	64
144	6550N 9300	E	<0.2	2.36	<5	60	10	0.53	<1	24	40	123	4.08	<10	1.12	370	<1	0.03	22	1330	10	<5	<20	81	0.14	<10	156	<10	7	58
145	6550N 9350	E	<0.2	2.49	<5	65	10	0.60	<1	26	36	87	3.53	<10	1.41	361	<1	0.02	23	1790	10	<5	<20	85	0.14	<10	138	<10	8	65
146	6550N 9400	E	<0.2	3.03	<5	110	<5	0.52	<1	27	49	138	4.27	10	1.42	472	<1	0.02	26	2010	12	<5	<20	66	0.13	<10	147	<10	8	81
147	6550N 9450	E	<0.2	2.34	<5	100	10	0.48	<1	23	38	78	3.43	<10	0.99	912	<1	0.02	21	1730	12	<5	<20	62	0.12	10	113	<10	7	76
148	6550N 9500	E	<0.2	2.38	<5	65	10	0.52	<1	25	43	84	3.84	<10	1.23	575	<1	0.02	21	1740	10	<5	<20	64	0.13	<10	137	<10	8	73
149	6550N 9550	E	<0.2	2.87	<5	50	5	0.68	<1	27	56	100	5.11	10	1.44	416	<1	0.03	26	2720	12	<5	<20	90	0.14	<10	186	<10	9	78
150	6550N 9600	E	<0.2	2.55	<5	75	10	0.53	<1	26	49	73	4.43	10	1.19	437	<1	0.03	24	1670	12	<5	<20	80	0.14	<10	168	<10	8	63
151	6550N 9650	E	<0.2	2.40	<5	75	10	0.42	<1	23	53	51	3.90	10	0.95	496	<1	0.03	26	1300	10	<5	<20	49	0.11	<10	121	<10	7	68
152	6550N 9700	E	<0.2	2.57	<5	85	10	0.75	<1	31	46	137	4.53	10	1.79	604	<1	0.02	25	2690	10	<5	<20	81	0.16	10	188	<10	8	80
153	6550N 9750	E	<0.2	3.53	<5	180	10	0.63	<1	35	56	123	5.86	20	2.08	683	<1	0.02	30	2170	12	<5	<20	61	0.16	<10	245	<10	9	90
154	6550N 9800	E	<0.2	2.40	<5	115	5	1.17	<1	29	85	101	4.93	20	1.53	592	<1	0.03	40	1220	6	<5	<20	163	0.12	<10	169	<10	11	63
155	6550N 9850	E	<0.2	2.52	<5	120	5	0.58	<1	28	112	62	5.00	10	1.36	465	<1	0.03	44	2170	10	<5	<20	60	0.12	<10	146	<10	7	85
156	6550N 9900	E	<0.2	3.63	<5	240	10	0.98	<1	34	135	159	5.68	20	1.95	1172	<1	0.03	62	1140	12	<5	<20	100	0.14	<10	176	<10	13	82
157	6550N 9950	E B/L	<0.2	2.76	<5	180	10	0.84	<1	35	129	120	4.85	10	2.08	821	<1	0.03	63	1380	12	<5	<20	85	0.14	<10	172	<10	10	67
158	6850N 7650	E	<0.2	2.08	<5	60	10	0.32	<1	21	121	45	3.85	<10	1.40	428	<1	0.02	45	560	10	<5	<20	25	0.12	<10	94	<10	6	44
159	6850N 7700	E	<0.2	2.68	<5	70	10	0.21	<1	24	59	63	4.75	<10	1.39	561	<1	0.02	24	680	10	<5	<20	16	0.12	10	105	<10	6	62
160	6850N 7750	E	0.4	3.20	<5	85	5	0.92	<1	21	108	65	3.43	10	1.38	350	<1	0.03	67	1360	14	<5	<20	26	0.08	<10	82	<10	11	89
161	6850N 7800	E	<0.2	2.09	<5	80	5	0.36	<1	18	57	56	4.17	10	1.00	295	<1	0.02	21	400	10	<5	<20	27	0.11	<10	120	<10	8	53
162	6850N 7850	E	<0.2	2.63	<5	130	10	0.32	<1	23	94	56	4.61	10	1.12	732	<1	0.02	38	950	12	<5	<20	21	0.09	<10	121	<10	7	84
163	6850N 7900	E	<0.2	2.62	<5	190	<5	0.34	<1	27	64	94	5.10	10	1.26	1140	<1	0.03	26	1080	10	<5	<20	21	0.09	10	163	<10	6	78
164	6850N 7950	E	<0.2	3.02	<5	190	<5	0.24	<1	36	95	134	7.99	20	1.17	915	<1	0.02	40	1110	6	<5	<20	15	0.09	10	272	<10	8	70
165	6850N 8000	E	<0.2	2.46	<5	160	5	0.37	<1	26	139	74	5.76	10	1.22	1277	<1	0.03	53	1040	8	<5	<20	21	0.09	10	191	<10	5	71

BRIGHT STAR VENTURES

ICP CERTIFICATE OF ANALYSIS AK 2002-326

ECO TECH LABORATORY LTD.

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe%	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
166	6850N 8050 E	<0.2	1.99	<5	40	10	0.21	<1	17	181	22	3.62	<10	0.89	410	<1	0.02	31	680	10	<5	<20	15	0.09	10	101	<10	5	40
167	6850N 8100 E	<0.2	1.35	<5	30	10	0.20	<1	18	370	8	3.08	<10	1.01	162	<1	0.02	42	270	6	5	<20	7	0.11	<10	78	<10	5	32
168	6850N 8150 E	<0.2	1.94	<5	95	15	0.34	<1	16	53	28	4.19	10	0.67	225	<1	0.02	17	560	8	<5	<20	29	0.12	<10	121	<10	7	42
169	6850N 8200 E	<0.2	2.29	<5	180	5	0.70	<1	22	91	46	4.11	10	0.95	338	<1	0.03	30	500	14	<5	<20	36	0.10	<10	144	<10	8	55
170	6850N 8250 E	<0.2	2.32	5	185	<5	0.77	<1	28	146	42	4.80	10	1.14	590	<1	0.03	67	570	14	<5	<20	37	0.11	<10	163	<10	9	57
171	6850N 8300 E	<0.2	1.79	<5	45	15	0.58	<1	41	137	10	7.08	10	1.95	189	<1	0.04	60	280	8	<5	<20	10	0.20	<10	254	<10	9	52
172	6850N 8350 E	<0.2	2.14	<5	105	10	0.37	<1	33	117	35	6.78	10	1.20	224	<1	0.03	45	210	8	<5	<20	26	0.16	<10	222	<10	9	45
173	6850N 8400 E	<0.2	2.14	35	175	10	0.67	<1	36	182	25	8.24	10	1.51	185	<1	0.03	93	180	8	<5	<20	20	0.18	<10	288	<10	12	50
174	6850N 8450 E	<0.2	2.08	35	155	15	0.72	<1	45	135	29	>10	20	1.38	1029	<1	0.03	122	180	6	<5	<20	17	0.19	<10	363	<10	12	53
175	6850N 8500 E	<0.2	2.30	<5	105	15	0.50	<1	44	144	25	9.60	20	1.70	321	<1	0.04	66	420	4	<5	<20	13	0.18	<10	368	<10	9	56
176	6850N 8550 E	<0.2	1.83	10	95	10	0.48	<1	39	296	28	7.81	20	1.34	216	<1	0.04	80	210	2	<5	<20	24	0.18	<10	268	<10	12	49
177	6850N 8600 E	<0.2	1.42	<5	60	10	0.38	<1	21	182	13	3.51	<10	0.89	137	<1	0.03	45	370	8	<5	<20	22	0.11	<10	86	<10	7	35
178	6850N 8650 E	<0.2	1.99	10	195	5	0.84	<1	40	304	46	6.64	20	1.93	418	<1	0.04	100	280	4	<5	<20	29	0.14	<10	242	<10	13	43
179	6850N 8700 E	<0.2	2.01	10	105	10	0.45	<1	32	231	47	4.53	10	1.09	602	<1	0.04	80	360	10	<5	<20	22	0.13	<10	158	<10	11	44
180	6850N 8750 E	<0.2	2.03	<5	75	10	0.60	<1	25	73	51	4.83	10	1.24	333	<1	0.03	27	750	8	<5	<20	58	0.15	<10	171	<10	11	59
181	6850N 8800 E	<0.2	2.51	20	135	10	0.70	<1	30	169	79	4.77	20	1.18	726	<1	0.04	81	470	12	<5	<20	32	0.14	<10	163	<10	16	43
182	6850N 8850 E	<0.2	2.37	10	140	10	0.58	<1	23	102	63	4.21	10	0.90	259	<1	0.03	50	550	12	<5	<20	48	0.12	<10	140	<10	11	42
183	6850N 8900 E	<0.2	1.95	15	145	5	0.95	<1	34	209	68	6.22	20	1.45	599	<1	0.04	66	550	6	<5	<20	36	0.12	<10	243	<10	13	42
184	6850N 8950 E	<0.2	2.11	25	125	10	0.92	<1	37	327	68	8.20	20	1.52	365	<1	0.05	91	530	4	<5	<20	34	0.17	<10	314	<10	14	52
185	6850N 9000 E	<0.2	1.19	25	230	<5	1.94	<1	27	147	56	4.73	10	1.10	1562	<1	0.04	62	750	4	<5	<20	43	0.08	<10	128	<10	8	35
186	6850N 9050 E	<0.2	1.85	20	145	<5	1.04	<1	30	138	59	6.34	20	1.36	1359	<1	0.05	47	1210	6	<5	<20	76	0.12	<10	181	<10	13	45
187	6850N 9100 E	<0.2	2.22	<5	115	5	0.73	<1	21	53	49	3.46	10	1.24	441	<1	0.03	28	610	14	<5	<20	69	0.11	<10	110	<10	9	67
188	6850N 9150 E	<0.2	2.26	<5	80	10	0.52	<1	22	48	82	3.80	10	1.11	293	<1	0.03	20	1690	10	<5	<20	71	0.13	<10	143	<10	9	53
189	6850N 9200 E	<0.2	2.03	<5	50	5	0.40	<1	20	37	50	3.75	<10	0.81	235	<1	0.03	15	1780	12	<5	<20	54	0.14	<10	139	<10	8	69
190	6850N 9250 E	<0.2	2.71	<5	100	10	0.56	<1	26	51	108	4.02	10	1.40	372	<1	0.03	27	1890	14	<5	<20	64	0.12	<10	139	<10	9	68
191	6850N 9300 E Talus	No Sample		<5	105	5	0.59	<1	27	46	107	4.11	10	1.38	356	<1	0.03	25	2360	14	<5	<20	73	0.13	<10	148	<10	10	77
192	6850N 9350 E	<0.2	2.85	<5	90	5	0.57	<1	27	49	112	4.05	10	1.40	387	<1	0.03	25	1830	14	<5	<20	80	0.14	<10	147	<10	10	72
193	6850N 9400 E	<0.2	2.83	<5	90	5	0.57	<1	27	49	112	4.05	10	1.40	387	<1	0.03	25	1830	14	<5	<20	80	0.14	<10	147	<10	10	72
194	6850N 9450 E	<0.2	2.76	<5	55	<5	0.66	<1	26	47	179	3.96	10	1.45	544	<1	0.03	23	1060	14	<5	<20	70	0.16	<10	166	<10	15	59
195	6850N 9500 E	<0.2	2.53	<5	170	5	0.69	<1	28	45	141	4.30	10	1.46	451	<1	0.03	22	1640	12	<5	<20	82	0.14	<10	167	<10	9	72
196	6850N 9550 E	<0.2	1.92	<5	50	10	0.72	<1	26	39	50	3.47	<10	1.35	574	<1	0.02	19	1740	10	<5	<20	104	0.14	<10	149	<10	10	58
197	6850N 9600 E	<0.2	2.25	<5	65	5	0.59	<1	25	48	65	4.20	10	1.23	321	<1	0.03	21	1340	10	<5	<20	77	0.14	<10	177	<10	9	65
198	6850N 9650 E	<0.2	2.78	<5	55	<5	1.01	<1	34	48	604	4.60	10	1.85	621	<1	0.03	28	1580	12	<5	<20	113	0.18	<10	206	<10	16	77
199	6850N 9700 E	<0.2	2.29	<5	100	5	0.85	<1	27	78	80	4.39	10	1.38	510	<1	0.03	35	1180	10	<5	<20	95	0.11	<10	134	<10	11	70
200	6850N 9750 E	<0.2	3.14	<5	225	<5	0.85	<1	22	67	133	4.09	20	1.04	700	<1	0.04	40	690	14	<5	<20	102	0.10	<10	118	<10	18	63

BRIGHT STAR VENTURES

ICP CERTIFICATE OF ANALYSIS AK 2002-326

ECO TECH LABORATORY LTD.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
201	6850N 9800 E	<0.2	3.41	<5	230	<5	0.68	<1	21	74	128	4.66	20	1.00	627	<1	0.05	46	780	16	<5	<20	75	0.10	<10	123	<10	16	75
202	6850N 9850 E	<0.2	1.84	<5	170	<5	1.01	<1	17	54	65	3.23	20	0.81	675	<1	0.03	28	1270	10	<5	<20	108	0.07	<10	94	<10	13	61
203	6850N 9900 E	<0.2	2.25	<5	140	<5	1.13	<1	33	103	132	5.22	20	1.91	876	<1	0.04	47	2130	8	<5	<20	100	0.13	<10	172	<10	13	73
204	6850N 9950 E	<0.2	2.30	<5	85	5	0.75	<1	32	106	132	5.53	10	1.67	435	<1	0.03	41	1850	8	<5	<20	98	0.14	<10	185	<10	9	61
205	7150N 7650 E	<0.2	2.38	<5	85	5	0.29	<1	25	105	59	4.76	10	1.07	639	<1	0.03	38	1010	12	<5	<20	20	0.11	<10	144	<10	7	74
206	7150N 7700 E	<0.2	2.63	<5	150	<5	0.61	<1	37	91	124	7.27	20	1.07	1688	<1	0.04	40	1990	8	<5	<20	23	0.10	<10	260	<10	8	98
207	7150N 7750 E	<0.2	2.51	<5	55	<5	0.43	<1	30	101	309	6.39	10	1.44	248	<1	0.05	40	330	10	<5	<20	27	0.18	<10	245	<10	11	57
208	7150N 7800 E	<0.2	1.78	<5	65	15	0.55	<1	28	32	16	4.88	<10	1.63	197	<1	0.08	19	320	10	<5	<20	20	0.22	<10	236	<10	13	56
209	7150N 7850 E	<0.2	3.01	<5	60	15	0.35	<1	35	70	30	6.09	10	1.77	362	<1	0.04	33	340	14	<5	<20	20	0.19	<10	252	<10	11	69
210	7150N 7900 E	<0.2	2.35	<5	70	10	0.52	<1	29	107	33	5.87	10	1.27	398	<1	0.04	37	370	12	<5	<20	24	0.17	<10	223	<10	11	56
211	7150N 7950 E	<0.2	2.28	<5	65	10	0.62	<1	24	95	42	4.77	10	0.96	534	<1	0.04	34	340	12	<5	<20	34	0.14	<10	165	<10	11	53
212	7150N 8000 E	<0.2	2.09	<5	110	<5	0.77	<1	18	151	120	4.21	10	0.54	255	<1	0.03	31	480	10	<5	<20	30	0.09	<10	123	<10	10	33
213	7150N 8050 E	0.4	2.01	<5	275	<5	1.74	<1	16	273	215	2.53	10	0.45	3677	<1	0.04	47	810	12	<5	<20	44	0.09	<10	89	<10	12	23
214	7150N 8100 E	<0.2	2.14	<5	100	10	0.72	<1	24	118	38	4.77	10	0.94	252	<1	0.03	36	400	10	<5	<20	43	0.12	<10	157	<10	10	47
215	7150N 8150 E	<0.2	2.77	<5	165	10	0.63	<1	28	216	57	5.49	20	0.99	659	<1	0.04	68	420	12	<5	<20	27	0.13	<10	181	<10	17	50
216	7150N 8200 E	<0.2	1.61	<5	70	15	0.33	<1	22	116	11	6.09	10	0.57	117	<1	0.03	30	320	6	<5	<20	14	0.15	<10	194	<10	10	28
217	7150N 8250 E	<0.2	1.27	<5	40	15	0.25	<1	19	65	16	4.91	<10	0.64	103	<1	0.03	19	200	6	<5	<20	19	0.16	<10	172	<10	9	31
218	7150N 8300 E	<0.2	1.56	<5	45	10	0.33	<1	40	102	40	9.73	20	1.44	177	<1	0.03	41	130	2	<5	<20	2	0.24	<10	365	<10	12	36
219	7150N 8350 E	<0.2	1.93	<5	45	15	0.22	<1	47	90	11	>10	20	1.71	137	<1	0.02	50	80	2	<5	<20	3	0.21	<10	395	<10	11	45
220	7150N 8400 E	<0.2	2.30	<5	35	10	0.25	<1	63	135	10	>10	20	1.78	599	<1	0.02	69	260	<2	<5	<20	1	0.19	10	421	<10	10	66
221	7150N 8450 E	<0.2	1.75	<5	10	20	0.83	1	78	313	14	>10	20	3.50	328	<1	0.03	140	<10	<2	<5	<20	<1	0.34	<10	540	<10	16	67
222	7150N 8500 E	<0.2	1.11	<5	85	10	0.54	1	29	218	13	7.10	10	1.04	570	<1	0.07	49	640	4	<5	<20	15	0.19	<10	286	<10	10	51
223	7150N 8550 E	<0.2	1.93	35	140	<5	1.35	<1	19	150	112	3.40	10	0.84	788	<1	0.06	49	710	10	<5	<20	35	0.09	<10	151	<10	14	35
224	7150N 8600 E	<0.2	2.13	50	120	5	1.43	<1	48	188	77	9.28	20	2.14	486	<1	0.06	70	430	4	<5	<20	22	0.18	<10	379	<10	14	55
225	7150N 8650 E	<0.2	1.46	<5	60	15	0.64	<1	38	366	20	8.98	20	1.70	166	<1	0.05	77	180	2	<5	<20	20	0.25	<10	351	<10	13	42
226	7150N 8700 E	<0.2	2.23	<5	115	10	0.76	<1	22	68	58	4.33	10	0.89	295	<1	0.03	29	570	10	<5	<20	51	0.12	<10	132	<10	12	38
227	7150N 8750 E	<0.2	2.10	<5	75	5	0.71	<1	21	74	55	4.50	10	0.94	293	<1	0.03	28	770	10	<5	<20	52	0.11	<10	140	<10	9	156
228	7150N 8800 E	<0.2	2.74	<5	65	10	0.32	<1	19	51	36	3.84	<10	0.60	257	<1	0.03	19	1490	16	<5	<20	36	0.12	<10	115	<10	8	54
229	7150N 8850 E	<0.2	1.93	<5	60	5	0.56	<1	26	89	70	5.03	10	1.01	350	<1	0.03	32	1460	8	<5	<20	54	0.11	<10	158	<10	8	49
230	7150N 8900 E	<0.2	1.88	<5	75	5	0.63	<1	18	71	41	4.22	10	0.79	191	<1	0.03	24	1010	10	<5	<20	52	0.11	<10	134	<10	8	37
231	7150N 8950 E	<0.2	1.66	<5	60	10	0.43	<1	18	109	25	4.01	<10	0.83	202	<1	0.03	30	510	8	<5	<20	45	0.12	<10	133	<10	7	38
232	7150N 9000 E	<0.2	2.04	<5	65	5	0.70	<1	24	81	69	4.51	10	1.33	506	<1	0.03	30	1640	8	<5	<20	69	0.12	<10	155	<10	9	54
233	7150N 9050 E	<0.2	2.12	<5	65	10	0.50	<1	20	60	54	4.25	10	0.87	229	<1	0.03	21	1180	10	<5	<20	61	0.11	<10	145	<10	8	46
234	7150N 9100 E	<0.2	3.55	<5	205	<5	0.67	<1	25	64	153	4.45	10	1.18	1169	<1	0.04	43	800	18	<5	<20	57	0.12	<10	138	<10	11	77
235	7150N 9150 E	<0.2	2.40	<5	120	5	0.48	<1	22	48	59	4.02	10	0.98	399	<1	0.03	23	1350	14	<5	<20	56	0.12	<10	132	<10	9	61

BRIGHT STAR VENTURES

ICP CERTIFICATE OF ANALYSIS AK 2002-326

ECO TECH LABORATORY LTD.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
236	7150N 9200 E	<0.2	2.13	<5	85	5	0.65	<1	24	56	72	4.46	10	1.28	352	<1	0.03	23	1420	10	<5	<20	65	0.12	<10	156	<10	9	53
237	7150N 9250 E	<0.2	2.66	<5	110	<5	0.77	<1	32	63	129	4.97	10	1.81	559	<1	0.03	30	1710	10	<5	<20	79	0.15	<10	191	<10	9	70
238	7150N 9300 E	<0.2	2.65	<5	90	5	0.74	<1	32	56	129	4.81	10	1.67	806	<1	0.03	29	2130	12	<5	<20	83	0.14	<10	186	<10	9	87
239	7150N 9350 E	<0.2	2.40	<5	145	5	0.90	<1	32	42	114	4.70	10	1.44	646	<1	0.03	24	2350	12	<5	<20	108	0.15	<10	196	<10	10	108
240	7150N 9400 E	<0.2	2.11	<5	185	10	0.73	<1	28	39	87	4.10	10	1.22	899	<1	0.03	21	1800	10	<5	<20	94	0.15	<10	155	<10	9	98
241	7150N 9450 E	<0.2	2.81	<5	115	5	0.83	<1	34	52	148	5.75	20	1.65	508	<1	0.03	28	2370	14	<5	<20	108	0.16	<10	224	<10	12	103
242	7150N 9500 E	<0.2	2.94	<5	100	5	1.17	<1	41	67	242	6.15	20	2.11	1197	<1	0.04	34	3340	12	<5	<20	131	0.17	<10	253	<10	13	132
243	7150N 9550 E	<0.2	3.02	<5	70	<5	1.43	<1	41	49	219	6.38	20	2.38	1094	<1	0.03	29	3950	10	<5	<20	143	0.16	<10	298	<10	14	109
244	7150N 9600 E	<0.2	2.62	<5	100	10	1.02	<1	36	68	140	5.15	20	1.88	885	<1	0.04	32	2260	14	<5	<20	137	0.16	<10	205	<10	12	94
245	7150N 9650 E	<0.2	3.05	<5	115	<5	1.29	<1	40	46	180	6.02	20	2.25	765	<1	0.06	27	4350	14	<5	<20	149	0.17	<10	264	<10	13	114
246	7150N 9700 E	<0.2	2.58	<5	95	10	0.97	<1	36	88	117	5.57	20	1.74	782	<1	0.05	39	2040	10	<5	<20	125	0.14	<10	214	<10	10	84
247	7150N 9750 E	<0.2	2.52	<5	105	5	1.41	<1	45	51	206	6.40	30	2.02	1693	<1	0.07	26	5380	10	<5	<20	149	0.16	<10	268	<10	15	116
248	7150N 9800 E	<0.2	2.91	<5	105	10	0.90	<1	46	175	105	6.41	10	2.47	687	<1	0.04	79	1320	10	<5	<20	157	0.18	<10	219	<10	9	78
249	7150N 9850 E	<0.2	2.59	<5	210	5	0.96	<1	28	84	131	4.33	20	1.24	868	<1	0.04	44	700	12	<5	<20	120	0.12	<10	141	<10	14	61
250	7150N 9900 E	<0.2	3.40	<5	170	10	1.23	<1	45	122	126	6.18	20	2.72	860	<1	0.06	66	2460	14	<5	<20	113	0.18	<10	202	<10	13	93
251	7150N 9950 E	<0.2	2.19	<5	105	5	0.73	<1	30	78	83	5.00	10	1.49	897	<1	0.03	36	1850	10	<5	<20	98	0.14	<10	174	<10	9	77

QC DATA:

Repeat:	Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	R5350N	9900 E	<0.2	2.71	<5	65	10	0.41	<1	24	40	100	4.03	10	1.16	406	<1	0.02	23	1510	16	<5	<20	30	0.11	<10	125	<10	7	67
10	5650N	7950 E	<0.2	2.94	<5	40	10	0.24	<1	27	179	49	4.05	<10	1.77	337	<1	0.02	77	580	12	<5	<20	11	0.11	10	94	<10	6	52
19	5650N	8400 E	<0.2	2.27	120	95	15	0.43	3	45	125	14	9.20	10	1.45	426	<1	0.04	68	360	4	<5	<20	9	0.15	<10	310	<10	6	67
28	5650N	8850 E	<0.2	2.20	<5	85	10	0.41	<1	23	96	44	4.24	<10	0.96	302	<1	0.03	36	1070	12	<5	<20	36	0.11	<10	116	<10	6	51
36	5650N	9250 E	<0.2	2.17	<5	65	5	0.43	<1	24	117	53	4.81	10	1.22	274	<1	0.02	38	1430	8	<5	<20	40	0.10	<10	139	<10	6	53
45	R5800N	10000 E	<0.2	2.97	<5	40	10	0.94	<1	44	28	91	4.55	20	2.84	1012	<1	0.02	27	2960	10	<5	<20	56	0.14	10	191	<10	10	120
54	5950N	8100 E	<0.2	2.78	<5	260	10	0.40	<1	27	53	87	4.67	10	1.81	865	<1	0.02	21	1910	10	<5	<20	20	0.11	<10	138	<10	6	96
63	5950N	8550 E	<0.2	1.49	<5	50	10	0.27	<1	25	109	16	6.30	10	1.06	174	<1	0.03	29	510	6	<5	<20	8	0.18	<10	240	<10	8	48
106	6250N	8700 E	<0.2	1.76	15	65	10	0.37	<1	21	302	30	3.54	<10	0.96	388	<1	0.03	52	470	8	<5	<20	41	0.10	<10	94	<10	6	58
115	6550N	7850 E	0.4	2.03	<5	70	10	0.29	<1	23	72	41	4.24	<10	1.02	1366	<1	0.03	31	840	10	<5	<20	20	0.11	10	110	<10	6	62
124	6550N	8300 E	<0.2	2.85	<5	70	10	0.45	<1	25	117	43	5.25	10	1.25	408	<1	0.04	35	830	12	<5	<20	41	0.14	<10	170	<10	9	68
133	6550N	8750 E	<0.2	1.27	<5	40	10	0.28	<1	21	330	10	2.72	<10	1.30	245	<1	0.02	60	580	8	<5	<20	16	0.09	10	68	<10	4	49
141	6550N	9150 E	<0.2	2.00	30	220	<5	1.18	<1	32	150	72	7.17	20	1.42	2065	<1	0.04	57	1200	2	<5	<20	72	0.12	<10	188	<10	13	46
150	6550N	9600 E	<0.2	2.55	<5	75	10	0.53	<1	26	49	73	4.43	10	1.19	437	<1	0.03	24	1670	12	<5	<20	80	0.14	<10	166	<10	8	63
159	R6850N	7700 E	<0.2	2.68	<5	70	10	0.21	<1	24	59	63	4.75	<10	1.39	561	<1	0.02	24	680	10	<5	<20	16	0.12	10	105	<10	6	62
168	6850N	8150 E	<0.2	1.94	<5	95	15	0.34	<1	16	53	28	4.19	10	0.67	225	<1	0.02	17	560	8	<5	<20	29	0.12	<10	121	<10	7	42
176	6850N	8550 E	<0.2	1.86	15	90	10	0.47	<1	39	302	29	7.93	20	1.35	216	<1	0.04	81	230	4	<5	<20	23	0.18	<10	272	<10	12	51

BRIGHT STAR VENTURES

ICP CERTIFICATE OF ANALYSIS AK 2002-326

ECO TECH LABORATORY LTD.

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
------	-------	----	------	----	----	----	------	----	----	----	----	------	----	------	----	----	------	----	---	----	----	----	----	------	---	---	---	---	----

QC DATA:

Repeat:		Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
185	6850N 9000 E	<0.2	1.13	20	230	<5	2.06	<1	26	140	56	4.32	10	1.01	1555	<1	0.04	60	790	4	<5	<20	43	0.07	<10	114	<10	8	33
194	6850N 9450 E	<0.2	2.76	<5	55	<5	0.63	<1	26	48	179	3.94	10	1.44	541	<1	0.03	24	1040	16	<5	<20	66	0.15	<10	165	<10	15	59
203	6850N 9900 E	<0.2	2.26	<5	135	5	1.12	<1	32	101	133	5.16	20	1.92	876	<1	0.04	48	2130	10	<5	<20	96	0.13	<10	172	<10	13	73
211	7150N 7950 E	<0.2	2.39	<5	65	10	0.63	<1	24	95	44	4.75	10	1.00	563	<1	0.04	35	370	12	<5	<20	33	0.14	<10	163	<10	12	54
220	7150N 8400 E	<0.2	2.24	<5	35	10	0.24	<1	62	133	10	>10	20	1.73	567	<1	0.02	68	250	<2	<5	<20	1	0.19	<10	431	<10	10	65
229	7150N 8850 E	<0.2	1.95	<5	60	<5	0.56	<1	25	90	73	5.05	10	1.02	354	<1	0.03	33	1510	8	<5	<20	53	0.11	<10	159	<10	8	49
238	7150N 9300 E	<0.2	2.71	<5	90	5	0.72	<1	33	57	134	4.87	10	1.71	823	<1	0.03	30	2100	14	<5	<20	79	0.14	<10	188	<10	9	89
246	7150N 9700 E	<0.2	2.69	<5	95	10	0.91	<1	38	85	123	5.50	20	1.81	818	<1	0.05	41	1850	12	<5	<20	117	0.16	<10	215	<10	11	88

Standard:

GEO '02		1.4	1.77	50	135	<5	1.64	<1	20	75	84	3.66	10	0.97	617	<1	0.04	34	680	24	<5	<20	46	0.09	<10	78	<10	11	74
GEO '02		1.6	1.81	55	140	<5	1.65	<1	20	75	87	3.69	10	1.00	625	<1	0.04	33	660	22	<5	<20	47	0.09	<10	79	<10	11	73
GEO '02		1.4	1.82	55	140	<5	1.68	<1	20	76	87	3.74	10	1.00	632	<1	0.04	34	660	24	<5	<20	49	0.10	<10	81	<10	11	73
GEO '02		1.4	1.85	50	140	<5	1.68	<1	21	76	87	3.71	10	1.00	628	<1	0.05	33	660	22	<5	<20	52	0.10	<10	82	<10	11	72
GEO '02		1.4	1.87	50	135	5	1.69	<1	20	77	87	3.69	10	1.01	622	<1	0.05	33	670	24	<5	<20	53	0.11	<10	83	<10	11	71
GEO '02		1.4	1.86	50	135	5	1.68	<1	20	77	87	3.68	10	1.00	618	<1	0.05	33	660	22	<5	<20	54	0.10	<10	83	<10	12	71

JJ/ejd
 dt/323/326/327
 XLS/02

ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

CERTIFICATE OF ANALYSIS AK 2002-388

BRIGHT STAR VENTURES
Suite 205 - 555 Burrard Street
Po Box 218
Vancouver, BC, V7X 1M7

18-Oct-02

ATTENTION: Bill Yeomans

No. of samples received: 106

Sample Type: Soil

Project #: Tulameen

Shipment #: Soil 3-2

Samples submitted by: Bright Star Ventures

ET #.	Tag #		Au (ppb)	Pd (ppb)	Pt (ppb)
1	L7750N 8400	E	<5	<5	15
2	L7750N 8450	E	<5	<5	25
3	L7750N 8500	E	<5	<5	35
4	L7750N 8550	E	<5	<5	25
5	L7750N 8600	E	<5	5	25
6	L7750N 8650	E	<5	5	25
7	L7750N 8700	E	<5	<5	130
8	L7750N 8750	E	<5	<5	60
9	L7750N 8800	E	<5	5	35
10	L7750N 8850	E	5	5	<5
11	L7750N 8900	E	5	<5	<5
12	L7750N 8950	E	<5	<5	<5
13	L7750N 9000	E	<5	10	<5
14	L7750N 9050	E	<5	5	5
15	L7750N 9100	E	<5	<5	<5
16	L7750N 9150	E	<5	<5	5
17	L7750N 9200	E	<5	5	5
18	L7750N 9250	E	<5	5	<5
19	L7750N 9300	E	<5	<5	10
20	L7750N 9350	E	<5	<5	10
21	L7750N 9400	E	<5	<5	5
22	L7750N 9450	E	<5	5	5
23	L8050N 8400	E	<5	<5	25
24	L8050N 8450	E	<5	<5	25
25	L8050N 8500	E	<5	10	5
26	L8050N 8550	E	<5	<5	5
27	L8050N 8600	E	<5	<5	20
28	L8050N 8650	E	<5	<5	15
29	L8050N 8700	E	<5	<5	10

BRIGHT STAR VENTURES AK2-388

18-Oct-02

ET #.	Tag #		Au (ppb)	Pd (ppb)	Pt (ppb)	
30	L8050N	8750	E	<5	<5	30
31	L8050N	8800	E	<5	<5	30
32	L8050N	8850	E	<5	15	10
33	L8050N	8900	E	5	<5	25
34	L8050N	8950	E	<5	<5	10
35	L8050N	9000	E	<5	<5	5
36	L8050N	9050	E	10	10	20
37	L8050N	9100	E	10	<5	<5
38	L8050N	9150	E	<5	5	<5
39	L8050N	9200	E	5	5	<5
40	L8050N	9250	E	<5	5	<5
41	L8050N	9300	E	<5	<5	10
42	L8050N	9350	E	15	5	<5
43	L8050N	9400	E	<5	10	<5
44	L8350N	8400	E	<5	<5	<5
45	L8350N	8450	E	5	5	15
46	L8350N	8500	E	<5	<5	15
47	L8350N	8550	E	<5	<5	20
48	L8350N	8600	E	<5	5	<5
49	L8350N	8650	E	5	<5	5
50	L8350N	8700	E	5	5	5
51	L8350N	8750	E	<5	<5	10
52	L8350N	8800	E	5	5	10
53	L8350N	8850	E	<5	<5	15
54	L8350N	8900	E	<5	5	<5
55	L8350N	8950	E	<5	<5	<5
56	L8350N	9000	E	<5	5	5
57	L8350N	9050	E	<5	<5	30
58	L8350N	9100	E	<5	5	15
59	L8350N	9150	E	<5	<5	<5
60	L8350N	9200	E	<5	5	5
61	L8350N	9250	E	<5	<5	15
62	L8350N	9300	E	<5	<5	15
63	L8350N	9350	E	5	5	15
64	L8350N	9400	E	5	10	<5
65	L8650N	8400	E	<5	5	10

66	L8650N	8450	E	<5	5	20
67	L8650N	8500	E	<5	5	<5
68	L8650N	8550	E	<5	10	5
69	L8650N	8600	E	<5	10	<5
70	L8650N	8650	E	<5	20	30
71	L8650N	8700	E	<5	25	20
72	L8650N	8750	E	<5	10	20
73	L8650N	8800	E	<5	<5	10
74	L8650N	8850	E	<5	<5	5
75	L8650N	8900	E	5	<5	35
76	L8650N	8950	E	<5	<5	5
77	L8650N	9000	E	<5	5	125

BRIGHT STAR VENTURES AK2-388

18-Oct-02

ET #.	Tag #			Au (ppb)	Pd (ppb)	Pt (ppb)
78	L8650N	9050	E	<5	5	<5
79	L8650N	9100	E	<5	5	5
80	L8650N	9150	E	<5	5	10
81	L8650N	9200	E	<5	<5	10
82	L8650N	9250	E	<5	5	10
83	L8650N	9300	E	<5	<5	15
84	L8650N	9350	E	10	5	15
85	L8950N	8400	E	<5	25	15
86	L8950N	8450	E	<5	10	40
87	L8950N	8500	E	<5	<5	20
88	L8950N	8550	E	5	10	15
89	L8950N	8600	E	<5	20	<5
90	L8950N	8650	E	5	15	20
91	L8950N	8700	E	<5	<5	20
92	L8950N	8750	E	5	<5	20
93	L8950N	8800	E	<5	5	30
94	L8950N	8850	E	<5	<5	15
95	L8950N	8900	E	<5	<5	15
96	L8950N	8950	E	<5	<5	15
97	L8950N	9000	E	5	<5	10
98	L8950N	9050	E	<5	<5	25
99	L8950N	9100	E	<5	5	50
100	L8950N	9150	E	<5	5	30
101	L8950N	9200	E	<5	<5	50
102	L8950N	9250	E	5	<5	35
103	L8950N	9300	E	<5	<5	40
104	L8950N	9350	E	5	<5	30
105	L8950N	9400	E	<5	<5	15
106	L8950N	9450	E	<5	<5	80

QC DATA:

Repeat:

1	L7750N	8400	E	<5	<5	20
10	L7750N	8850	E	<5	5	<5
21	L7750N	9400	E	<5	<5	5
31	L8050N	8800	E	<5	<5	40
44	L8350N	8400	E	<5	<5	<5
50	L8350N	8700	E	5	<5	15
63	L8350N	9350	E	<5	<5	15
71	L8650N	8700	E	<5	20	15
84	L8650N	9350	E	<5	<5	15
90	L8950N	8650	E	5	15	15

BRIGHT STAR VENTURES AK2-388

18-Oct-02

ET #.	Tag #	Au (ppb)	Pd (ppb)	Pt (ppb)
-------	-------	-------------	-------------	-------------

Standard:

PG101	60	550	270
PG101	70	540	290
PG101	70	540	270
PG101	70	540	290
PG101	60	540	270
PG101	70	560	280

JJ/kk

ECO TECH LABORATORY LTD.
Jutta Jealouse

October 18, 2002

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 2002-388

BRIGHT STAR VENTURES
Suite 205 - 555 Burrard Street
Po Box 218
Vancouver, BC, V7X 1M7

Phone: 250-573-5700
Fax : 250-573-4557

ATTENTION: Bill Yeomans

No. of samples received: 106

Sample Type: Soil

Project #: Tulameen

Shipment #: Soil 3-2

Samples submitted by: Bright Star Ventures

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
1	L7750N 8400	E	<0.2	0.49	<5	10	<5	0.11	<1	14	484	2	1.00	<10	1.01	148	<1	0.02	59	60	<2	<5	<20	1	0.04	<10	11	<10	<1	21
2	L7750N 8450	E	<0.2	0.83	<5	45	<5	0.25	<1	33	251	7	2.84	<10	1.48	558	<1	0.02	97	330	<2	<5	<20	4	0.08	<10	25	<10	1	38
3	L7750N 8500	E	<0.2	1.74	<5	50	<5	0.13	<1	21	168	12	3.43	<10	0.64	100	<1	0.03	68	710	4	<5	<20	6	0.15	<10	57	<10	4	49
4	L7750N 8550	E	<0.2	1.13	<5	70	5	0.16	<1	18	115	9	3.48	<10	0.47	104	<1	0.03	40	620	6	<5	<20	8	0.18	<10	68	<10	4	44
5	L7750N 8600	E	<0.2	2.41	100	350	5	0.33	<1	29	253	30	3.73	10	1.13	207	<1	0.03	324	160	2	<5	<20	14	0.14	<10	81	<10	5	46
6	L7750N 8650	E	<0.2	1.40	<5	60	5	0.18	<1	22	98	26	3.74	10	1.12	218	<1	0.03	57	390	<2	<5	<20	12	0.11	<10	84	<10	3	47
7	L7750N 8700	E	<0.2	1.08	<5	60	<5	0.17	<1	30	145	10	3.98	10	1.04	242	<1	0.03	72	290	<2	<5	<20	7	0.13	<10	77	<10	2	49
8	L7750N 8750	E	<0.2	1.76	<5	60	<5	0.29	<1	32	140	44	4.32	10	1.36	265	<1	0.03	66	750	<2	<5	<20	18	0.15	<10	116	<10	3	49
9	L7750N 8800	E	<0.2	1.26	<5	90	<5	0.25	<1	29	224	18	3.52	<10	1.41	249	<1	0.03	64	200	<2	<5	<20	10	0.12	<10	79	<10	3	43
10	L7750N 8850	E	<0.2	1.40	<5	40	<5	0.30	<1	20	71	64	4.05	10	0.90	230	<1	0.03	27	1260	<2	<5	<20	19	0.13	<10	117	<10	4	36
11	L7750N 8900	E	<0.2	1.79	<5	60	<5	0.17	<1	18	45	49	3.62	10	0.88	312	<1	0.03	18	1080	<2	<5	<20	14	0.13	<10	105	<10	4	44
12	L7750N 8950	E	<0.2	1.49	<5	105	<5	0.27	<1	20	52	75	3.46	10	0.91	429	<1	0.03	27	760	<2	<5	<20	19	0.11	<10	94	<10	3	47
13	L7750N 9000	E	<0.2	1.37	<5	55	<5	0.47	<1	21	50	74	3.47	10	1.18	412	<1	0.04	28	1110	<2	<5	<20	26	0.11	<10	95	<10	7	41
14	L7750N 9050	E	<0.2	2.59	<5	65	<5	0.41	<1	28	55	137	4.64	20	1.40	424	<1	0.03	29	1980	<2	<5	<20	29	0.17	<10	139	<10	6	75
15	L7750N 9100	E	<0.2	1.85	<5	105	<5	0.34	<1	24	50	62	4.08	10	0.97	502	<1	0.03	24	1310	<2	<5	<20	23	0.16	<10	120	<10	4	67
16	L7750N 9150	E	<0.2	1.38	<5	60	<5	0.23	<1	20	49	58	3.93	10	0.77	182	<1	0.03	22	810	<2	<5	<20	20	0.11	<10	103	<10	3	34
17	L7750N 9200	E	<0.2	1.58	<5	95	<5	0.30	<1	23	60	78	4.21	10	1.01	405	<1	0.03	28	430	<2	<5	<20	30	0.12	<10	113	<10	4	40
18	L7750N 9250	E	<0.2	2.69	10	250	<5	0.49	<1	26	81	246	4.64	30	1.15	399	<1	0.03	59	450	<2	<5	<20	49	0.14	<10	156	<10	18	48
19	L7750N 9300	E	<0.2	1.07	<5	50	<5	0.24	<1	14	36	32	3.06	<10	0.60	181	<1	0.03	15	830	<2	<5	<20	17	0.09	<10	83	<10	3	31
20	L7750N 9350	E	<0.2	1.73	<5	65	<5	0.17	<1	15	35	45	3.34	<10	0.56	176	<1	0.03	17	1360	<2	<5	<20	11	0.11	<10	84	<10	3	39
21	L7750N 9400	E	<0.2	2.56	<5	90	<5	0.17	<1	16	37	78	3.63	10	0.66	190	<1	0.03	20	1070	<2	<5	<20	14	0.12	<10	87	<10	9	40
22	L7750N 9450	E	<0.2	1.97	<5	100	<5	0.27	<1	17	36	72	3.13	10	0.85	752	<1	0.03	23	630	<2	<5	<20	18	0.11	<10	78	<10	6	46
23	L8050N 8400	E	<0.2	1.21	80	136	<5	0.43	<1	22	143	12	3.61	10	0.48	220	<1	0.03	87	440	<2	<5	<20	12	0.13	<10	89	<10	5	49
24	L8050N 8450	E	<0.2	1.79	45	100	<5	0.32	<1	20	96	23	3.15	10	0.69	487	<1	0.04	70	250	4	<5	<20	10	0.14	<10	100	<10	5	40
25	L8050N 8500	E	0.2	1.65	75	165	<5	0.72	<1	15	145	59	2.50	20	0.55	893	<1	0.04	83	570	<2	<5	<20	15	0.09	<10	85	<10	12	30

BRIGHT STAR VENTURES

ICP CERTIFICATE OF ANALYSIS AK 2002-388

ECO TECH LABORATORY LTD.

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
26	L8050N 8550	E	<0.2	1.84	30	95	<5	0.34	<1	17	79	20	3.92	10	0.53	163	<1	0.03	32	210	4	<5	<20	11	0.17	<10	117	<10	6	53
27	L8050N 8600	E	<0.2	1.20	<5	75	<5	0.17	<1	18	93	14	4.34	10	0.52	93	<1	0.03	27	390	<2	<5	<20	7	0.14	<10	119	<10	3	36
28	L8050N 8650	E	<0.2	1.50	<5	135	<5	0.48	<1	27	121	72	5.01	20	0.83	213	<1	0.03	52	170	<2	<5	<20	14	0.14	<10	144	<10	6	35
29	L8050N 8700	E	<0.2	1.65	25	130	<5	0.33	<1	16	113	32	2.98	10	0.55	196	<1	0.03	79	300	2	<5	<20	14	0.11	<10	75	<10	9	35
30	L8050N 8750	E	<0.2	1.76	80	165	<5	0.51	<1	23	148	39	4.04	20	0.69	139	<1	0.03	74	160	<2	<5	<20	19	0.13	<10	104	<10	10	31
31	L8050N 8800	E	<0.2	0.70	<5	50	<5	0.13	<1	14	105	9	2.80	<10	0.47	71	<1	0.03	31	60	<2	<5	<20	8	0.10	<10	70	<10	2	20
32	L8050N 8850	E	<0.2	1.39	<5	50	<5	0.12	<1	18	98	21	3.83	10	0.63	99	<1	0.03	37	440	<2	<5	<20	8	0.12	<10	96	<10	3	30
33	L8050N 8900	E	<0.2	1.39	<5	45	<5	0.14	<1	22	196	26	3.56	10	1.01	152	<1	0.03	49	360	<2	<5	<20	12	0.12	<10	89	<10	3	37
34	L8050N 8950	E	<0.2	1.50	<5	70	<5	0.17	<1	24	157	34	3.57	10	1.05	245	<1	0.03	47	380	<2	<5	<20	16	0.15	<10	98	<10	4	38
35	L8050N 9000	E	<0.2	2.22	<5	80	<5	0.21	<1	27	77	74	4.12	10	1.21	356	<1	0.03	61	800	<2	<5	<20	21	0.19	<10	129	<10	5	53
36	L8050N 9050	E	<0.2	2.21	<5	90	<5	0.28	<1	23	42	90	3.54	10	1.13	894	<1	0.03	22	1690	<2	<5	<20	23	0.19	<10	120	<10	5	71
37	L8050N 9100	E	<0.2	1.74	<5	130	<5	0.28	<1	22	31	82	3.00	<10	1.02	550	<1	0.03	17	1040	<2	<5	<20	27	0.17	<10	96	<10	5	49
38	L8050N 9150	E	<0.2	2.13	<5	150	<5	0.41	<1	30	58	131	4.45	20	1.40	702	<1	0.03	27	1880	<2	<5	<20	33	0.21	<10	161	<10	6	77
39	L8050N 9200	E	<0.2	2.38	<5	125	<5	0.58	<1	30	50	145	4.47	20	1.49	736	<1	0.03	33	2090	<2	<5	<20	43	0.17	<10	144	<10	6	86
40	L8050N 9250	E	<0.2	3.10	<5	85	5	1.13	<1	40	70	198	5.55	20	2.56	818	<1	0.03	45	2120	<2	<5	<20	32	0.24	<10	157	<10	7	106
41	L8050N 9300	E	<0.2	2.33	<5	95	5	0.54	<1	33	86	60	4.94	20	1.62	772	<1	0.03	46	1770	<2	<5	<20	25	0.18	<10	130	<10	5	88
42	L8050N 9350	E	<0.2	2.41	<5	105	<5	0.24	<1	24	104	62	4.50	20	1.08	242	<1	0.03	45	1800	<2	<5	<20	21	0.15	<10	109	<10	5	74
43	L8050N 9400	E	<0.2	1.22	<5	150	<5	0.25	<1	21	88	49	4.12	10	0.75	197	<1	0.03	40	570	<2	<5	<20	16	0.12	<10	106	<10	6	39
44	L8350N 8400	E	<0.2	1.66	<5	125	5	0.33	<1	22	113	41	4.21	20	0.73	212	<1	0.03	88	200	2	<5	<20	12	0.17	<10	143	<10	7	36
45	L8350N 8450	E	<0.2	1.44	<5	115	<5	0.23	<1	29	90	43	6.01	20	1.01	162	<1	0.03	37	110	<2	<5	<20	7	0.25	<10	241	<10	6	53
46	L8350N 8500	E	<0.2	1.47	<5	105	5	0.18	<1	26	71	25	4.81	10	1.00	480	<1	0.03	34	180	<2	<5	<20	8	0.19	<10	165	<10	5	42
47	L8350N 8550	E	<0.2	1.86	<5	120	<5	0.30	<1	24	86	53	4.52	20	0.94	341	<1	0.03	39	330	<2	<5	<20	10	0.14	<10	131	<10	4	43
48	L8350N 8600	E	<0.2	1.29	<5	75	<5	0.15	<1	18	61	24	4.27	10	0.55	125	<1	0.03	27	280	<2	<5	<20	7	0.13	<10	114	<10	3	39
49	L8350N 8650	E	<0.2	1.36	<5	95	<5	0.15	<1	15	57	23	3.97	10	0.47	99	<1	0.03	29	330	2	<5	<20	8	0.12	<10	109	<10	3	35
50	L8350N 8700	E	<0.2	1.87	<5	85	<5	0.14	<1	25	80	40	5.01	20	0.84	222	<1	0.03	41	260	<2	<5	<20	7	0.16	<10	129	<10	4	51
51	L8350N 8750	E	<0.2	2.06	<5	90	5	0.14	<1	17	64	27	3.46	10	0.63	291	<1	0.03	32	400	4	<5	<20	9	0.12	<10	82	<10	3	49
52	L8350N 8800	E	<0.2	1.48	<5	90	<5	0.14	<1	12	66	16	2.80	<10	0.42	265	<1	0.03	21	500	4	<5	<20	8	0.10	<10	67	<10	3	45
53	L8350N 8850	E	<0.2	2.57	<5	140	<5	0.37	<1	22	85	53	3.92	20	0.97	409	<1	0.03	55	280	2	<5	<20	17	0.12	<10	99	<10	10	47
54	L8350N 8900	E	<0.2	2.02	20	135	<5	0.30	<1	18	117	28	3.80	20	0.68	190	<1	0.03	32	170	2	<5	<20	15	0.10	<10	93	<10	6	40
55	L8350N 8950	E	<0.2	1.90	<5	255	<5	0.49	<1	17	67	47	3.35	20	0.86	648	<1	0.04	44	410	<2	<5	<20	23	0.11	<10	81	<10	7	43
56	L8350N 9000	E	<0.2	2.22	<5	160	<5	0.61	<1	14	54	56	2.97	20	0.77	681	<1	0.04	42	370	<2	<5	<20	36	0.10	<10	72	<10	7	48
57	L8350N 9050	E	<0.2	1.23	<5	60	<5	0.24	<1	18	68	23	2.96	10	0.82	542	<1	0.03	42	210	<2	<5	<20	19	0.09	<10	73	<10	4	39
58	L8350N 9100	E	<0.2	1.40	<5	75	<5	0.20	<1	31	84	30	4.09	10	1.07	440	<1	0.04	67	250	<2	<5	<20	15	0.11	<10	83	<10	3	44
59	L8350N 9150	E	<0.2	1.35	<5	70	<5	0.19	<1	20	68	33	3.35	10	0.82	674	<1	0.03	41	370	<2	<5	<20	14	0.10	<10	85	<10	4	42
60	L8350N 9200	E	<0.2	1.47	<5	70	<5	0.17	<1	16	61	20	3.99	10	0.55	143	<1	0.03	28	850	<2	<5	<20	9	0.13	<10	90	<10	3	43

BRIGHT STAR VENTURES

ICP CERTIFICATE OF ANALYSIS AK 2002-388

ECO TECH LABORATORY LTD.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
61	L8350N 9250	E	<0.2	1.53	10	140	<5	0.44	<1	21	80	37	3.76	20	0.92	314	<1	0.03	48	260	<2	<5	<20	17	0.10	<10	95	<10	4	32
62	L8350N 9300	E	<0.2	2.34	<5	210	<5	0.66	<1	29	96	92	4.32	20	1.34	1111	<1	0.03	89	330	<2	<5	<20	43	0.13	<10	112	<10	13	43
63	L8350N 9350	E	<0.2	1.38	<5	50	<5	0.16	<1	21	77	26	4.14	10	0.81	146	<1	0.03	40	510	<2	<5	<20	9	0.13	<10	107	<10	3	40
64	L8350N 9400	E	<0.2	1.31	<5	70	<5	0.27	<1	25	92	29	4.40	10	1.06	184	<1	0.03	47	680	<2	<5	<20	12	0.13	<10	117	<10	3	36
65	L8650N 8400	E	<0.2	2.35	<5	105	<5	0.16	<1	43	175	46	7.16	30	1.49	1389	<1	0.03	114	520	<2	<5	<20	9	0.20	<10	191	<10	7	78
66	L8650N 8450	E	<0.2	1.06	<5	90	5	0.19	<1	37	191	17	5.03	20	1.03	914	<1	0.03	63	260	<2	<5	<20	6	0.19	<10	129	<10	3	54
67	L8650N 8500	E	<0.2	1.89	<5	80	<5	0.19	<1	37	199	42	5.46	20	1.43	358	<1	0.03	76	140	<2	<5	<20	4	0.22	<10	183	<10	5	64
68	L8650N 8550	E	<0.2	1.74	<5	110	<5	0.25	<1	28	150	140	4.47	10	1.05	798	<1	0.03	56	220	<2	<5	<20	4	0.19	<10	160	<10	5	57
69	L8650N 8600	E	<0.2	1.93	<5	110	5	0.21	<1	36	163	33	5.80	20	1.38	549	<1	0.03	97	310	<2	<5	<20	6	0.24	<10	184	<10	5	69
70	L8650N 8650	E	<0.2	1.90	<5	60	5	0.16	<1	41	142	71	6.25	20	1.69	386	<1	0.03	74	130	<2	<5	<20	2	0.25	<10	236	<10	6	77
71	L8650N 8700	E	<0.2	2.14	<5	140	<5	0.46	<1	41	121	211	6.11	20	1.63	755	<1	0.03	87	290	<2	<5	<20	6	0.21	<10	233	<10	6	73
72	L8650N 8750	E	0.2	1.72	<5	145	<5	0.23	<1	32	142	39	4.58	10	1.21	554	<1	0.03	104	200	<2	<5	<20	6	0.16	<10	118	<10	4	51
73	L8650N 8800	E	0.2	1.92	15	215	<5	0.76	<1	27	202	51	2.91	20	0.87	1560	<1	0.04	200	540	<2	<5	<20	15	0.12	<10	74	<10	10	43
74	L8650N 8850	E	0.3	1.86	5	265	5	0.48	<1	17	106	28	3.00	20	0.79	543	<1	0.04	77	210	2	<5	<20	19	0.10	<10	73	<10	8	38
75	L8650N 8900	E	<0.2	1.59	<5	105	<5	0.15	<1	16	76	23	3.87	10	0.71	195	<1	0.03	38	700	<2	<5	<20	10	0.12	<10	92	<10	3	50
76	L8650N 8950	E	<0.2	2.41	<5	275	<5	0.43	<1	16	75	54	3.12	20	0.81	834	<1	0.04	91	290	4	<5	<20	26	0.12	<10	77	<10	11	44
77	L8650N 9000	E	<0.2	1.54	5	70	<5	0.33	<1	23	69	33	3.45	10	1.15	547	<1	0.04	62	270	<2	<5	<20	21	0.11	<10	95	<10	5	46
78	L8650N 9050	E	<0.2	2.02	<5	115	<5	0.51	<1	21	58	50	3.55	20	1.33	597	<1	0.04	59	470	<2	<5	<20	31	0.12	<10	107	<10	8	49
79	L8650N 9100	E	<0.2	1.45	<5	50	<5	0.19	<1	17	77	33	3.96	10	0.77	147	<1	0.03	30	660	<2	<5	<20	14	0.11	<10	109	<10	3	42
80	L8650N 9150	E	<0.2	1.88	<5	75	<5	0.23	<1	26	114	63	5.18	20	1.34	240	<1	0.03	46	730	<2	<5	<20	16	0.15	<10	164	<10	3	50
81	L8650N 9200	E	0.2	2.18	15	110	<5	0.54	<1	22	102	100	4.12	20	1.19	426	<1	0.03	56	330	<2	<5	<20	36	0.12	<10	131	<10	10	44
82	L8650N 9250	E	0.3	2.46	<5	160	<5	0.58	<1	19	65	93	3.36	20	0.61	436	<1	0.04	46	350	2	<5	<20	69	0.16	<10	99	<10	14	33
83	L8650N 9300	E	0.3	2.52	<5	165	<5	0.81	<1	26	91	123	4.15	20	1.39	1022	<1	0.03	62	410	<2	<5	<20	82	0.15	<10	119	<10	15	60
84	L8650N 9350	E	<0.2	2.07	<5	105	<5	0.29	<1	27	83	61	4.15	20	1.44	402	<1	0.03	43	310	<2	<5	<20	21	0.14	<10	109	<10	4	42
85	L8950N 8400	E	<0.2	2.38	<5	225	<5	0.98	<1	22	183	34	4.11	20	1.20	331	<1	0.03	115	580	<2	<5	<20	18	0.13	<10	164	<10	7	46
86	L8950N 8450	E	<0.2	2.09	<5	60	<5	0.16	<1	39	123	30	6.11	20	1.69	512	<1	0.03	107	680	<2	<5	<20	6	0.19	<10	188	<10	4	74
87	L8950N 8500	E	<0.2	1.61	<5	100	<5	0.27	<1	35	152	25	5.39	20	1.15	751	<1	0.03	86	430	<2	<5	<20	7	0.18	<10	152	<10	4	62
88	L8950N 8550	E	<0.2	2.04	<5	85	5	0.21	<1	35	178	40	6.19	20	1.35	430	<1	0.03	89	340	<2	<5	<20	5	0.22	<10	196	<10	5	66
89	L8950N 8600	E	<0.2	1.94	<5	95	5	0.26	1	48	298	18	7.73	20	1.96	829	<1	0.03	108	90	<2	<5	<20	2	0.30	<10	297	<10	6	72
90	L8950N 8650	E	<0.2	2.44	<5	100	5	0.14	1	46	105	82	8.67	30	1.84	370	<1	0.03	110	90	<2	<5	<20	4	0.26	<10	328	<10	5	67
91	L8950N 8700	E	<0.2	1.86	<5	110	<5	0.21	<1	36	90	28	4.85	20	1.29	1409	<1	0.03	98	590	<2	<5	<20	11	0.15	<10	125	<10	4	64
92	L8950N 8750	E	<0.2	2.21	<5	125	<5	0.31	<1	37	110	33	5.11	20	1.62	1244	<1	0.03	92	590	<2	<5	<20	9	0.19	<10	141	<10	4	76
93	L8950N 8800	E	<0.2	2.05	<5	160	<5	0.35	<1	42	119	35	5.93	20	1.81	1024	<1	0.03	85	180	<2	<5	<20	6	0.21	<10	202	<10	5	65
94	L8950N 8850	E	0.2	2.40	<5	235	<5	0.77	<1	35	84	47	3.85	20	1.28	1645	<1	0.04	262	660	<2	<5	<20	15	0.13	<10	68	<10	8	72
95	L8950N 8900	E	<0.2	2.21	25	150	<5	0.54	<1	19	74	43	3.29	20	0.83	931	<1	0.03	113	640	2	<5	<20	21	0.09	<10	66	<10	11	62

BRIGHT STAR VENTURES

ICP CERTIFICATE OF ANALYSIS AK 2002-388

ECO TECH LABORATORY LTD.

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
96	L8950N 8950	E	<0.2	2.17	10	105	<5	0.48	<1	21	76	43	3.43	20	1.20	805	<1	0.03	141	690	<2	<5	<20	22	0.10	<10	62	<10	14	55
97	L8950N 9000	E	<0.2	1.75	<5	110	<5	0.27	<1	24	55	41	3.41	20	1.17	968	<1	0.03	92	380	<2	<5	<20	21	0.10	<10	66	<10	8	52
98	L8950N 9050	E	<0.2	2.13	10	110	<5	0.52	<1	40	84	62	4.26	30	1.99	1217	<1	0.03	166	740	<2	<5	<20	24	0.11	<10	65	<10	12	59
99	L8950N 9100	E	<0.2	1.68	15	75	<5	0.32	<1	49	107	45	4.59	20	2.54	1147	<1	0.03	188	850	<2	<5	<20	18	0.11	<10	62	<10	10	54
100	L8950N 9150	E	<0.2	1.71	<5	90	<5	0.21	<1	57	87	37	5.21	20	2.63	1220	<1	0.03	190	640	<2	<5	<20	15	0.14	<10	65	<10	7	57
101	L8950N 9200	E	<0.2	1.40	<5	80	<5	0.18	<1	76	94	35	6.11	20	4.39	1279	<1	0.03	301	600	<2	<5	<20	13	0.15	<10	54	<10	6	57
102	L8950N 9250	E	<0.2	1.76	<5	85	<5	0.17	<1	71	72	44	5.85	30	3.45	1398	<1	0.03	290	620	<2	<5	<20	16	0.15	<10	65	<10	10	62
103	L8950N 9300	E	<0.2	1.67	<5	90	<5	0.19	<1	84	110	34	5.92	20	3.81	1539	<1	0.03	331	460	<2	<5	<20	13	0.15	<10	50	<10	6	54
104	L8950N 9350	E	<0.2	1.30	<5	85	<5	0.16	<1	58	121	30	5.38	20	2.13	1300	<1	0.03	224	210	<2	<5	<20	13	0.14	<10	57	<10	3	46
105	L8950N 9400	E	<0.2	1.51	<5	70	<5	0.11	<1	52	91	30	4.72	10	2.30	821	<1	0.03	316	260	<2	<5	<20	8	0.13	<10	49	<10	2	53
106	L8950N 9450	E	<0.2	1.48	<5	100	<5	0.16	<1	39	127	15	3.69	10	1.63	1111	<1	0.03	144	380	<2	<5	<20	9	0.14	<10	53	<10	2	62

QC DATA:

Repeat:																														
1	L7750N 8400	E	<0.2	0.51	<5	10	<5	0.10	<1	14	484	3	1.03	<10	1.03	144	<1	0.02	58	70	<2	<5	<20	1	0.04	<10	12	<10	<1	21
10	L7750N 8950	E	<0.2	1.45	<5	50	<5	0.31	<1	20	65	67	3.96	10	0.91	234	<1	0.03	27	1240	<2	<5	<20	21	0.13	<10	116	<10	4	36
19	L7750N 9300	E	<0.2	1.07	<5	55	<5	0.24	<1	14	37	31	3.11	<10	0.60	181	<1	0.03	14	840	<2	<5	<20	17	0.10	<10	85	<10	3	31
28	L8050N 8650	E	<0.2	1.53	<5	135	<5	0.49	<1	28	125	75	5.17	20	0.86	212	<1	0.03	53	160	<2	<5	<20	14	0.14	<10	150	<10	6	35
36	L8050N 9050	E	<0.2	2.17	<5	90	5	0.27	<1	24	42	87	3.54	10	1.12	887	<1	0.03	20	1660	<2	<5	<20	22	0.19	<10	119	<10	5	73
45	L8350N 8450	E	<0.2	1.42	<5	115	5	0.22	<1	29	90	42	5.97	20	0.99	157	<1	0.03	36	120	<2	<5	<20	6	0.26	<10	240	<10	6	51
54	L8350N 8900	E	<0.2	2.07	20	140	<5	0.31	<1	18	119	29	3.82	20	0.69	201	<1	0.03	33	180	2	<5	<20	15	0.10	<10	93	<10	6	39
63	L8350N 9350	E	<0.2	1.37	<5	50	<5	0.15	<1	21	78	26	4.13	10	0.80	145	<1	0.03	43	520	<2	<5	<20	8	0.12	<10	106	<10	3	40
71	L8650N 8700	E	<0.2	2.26	<5	145	<5	0.47	<1	42	122	227	6.17	20	1.71	794	<1	0.03	89	320	<2	<5	<20	6	0.22	<10	237	<10	6	75
80	L8650N 9150	E	<0.2	1.86	<5	75	<5	0.22	<1	25	110	61	4.99	20	1.32	233	<1	0.03	43	720	<2	<5	<20	16	0.14	<10	158	<10	3	49
89	L8950N 8600	E	<0.2	1.94	<5	100	10	0.26	<1	47	286	18	7.41	20	1.95	853	<1	0.03	109	100	<2	<5	<20	2	0.29	<10	287	<10	6	73

Standard:

GEO 02	1.4	1.49	55	135	<5	1.45	<1	18	55	87	3.31	20	0.93	571	<1	0.04	27	610	14	<5	<20	39	0.13	<10	67	<10	8	68
GEO 02	1.5	1.43	50	130	<5	1.43	<1	18	53	91	3.23	20	0.91	560	<1	0.04	28	580	14	<5	<20	38	0.12	<10	65	<10	8	67
GEO 02	1.4	1.44	45	130	<5	1.42	<1	18	53	91	3.23	20	0.92	565	<1	0.04	33	590	12	<5	<20	38	0.13	<10	64	<10	8	69

JJ/kk
df/388
XLS/02

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

APPENDIX C

STATEMENT OF QUALIFICATIONS – WILLIAM C. YEOMANS

I, William C. Yeomans, hereby certify the following:

1. I am an independent consulting geologist, employed by Yeomans Geological Services, with office at 3225 Oriole Drive, Westbank, B.C., V4T 1A4

2. I earned a Bachelor of Science (Hons.) in Geology in 1982 at Queen's University in Kingston, Ontario, Canada.

3. I am a Professional Geoscientist registered with The Association of Professional Engineers and Geoscientists of the Province of British Columbia, registration No. 27187.

4. I am a Qualified Person (QP) as outlined in National Instrument 43-101 of the Canadian Securities Administrators (CSA).

5. I have read *National Instrument 43-101 and Form 43-101F1*.

6. I have practiced my profession for 20 years, and I am experienced in mineral exploration throughout the Americas. I have managed exploration programs encompassing planning, setting up and supervising of the following: drilling; logging; sampling and laboratory protocols for reverse circulation, diamond drill core, planning and execution of regional and detailed geochemistry and geological surveys, database development and management in several countries. I have integrated geological, geochemical, and geophysical data modeling utilizing GIS and other software.

7. The geological report dated March 18th , 2003 and titled "Bright Star Ventures 2002 Summary of the PGE Exploration Program for the Tulameen Ultramafic Complex, Similkameen District, South Central British Columbia, Canada," is a compilation of data provided to me by Bright Star Ventures Ltd.

8. This report was prepared for Bright Star Ventures Ltd. and is based on data provided to me by the company, which are believed to be accurate. Although all reasonable care has been taken in the preparation of this report.

9. I am not independent should the issuer apply all of the tests in Section 1.5 of NI43-101. I own options to purchase 150,000 shares of Bright Star Ventures Ltd. I own no other interest in any company or entity that owns or controls an interest in the properties that comprise the Tulameen Ultramafic Project.

10. I hereby give permission to Bright Star Ventures Ltd. to use this report in its complete and unedited form. Permission must be obtained from me before publication of any excerpt or summary from this report. The author is not responsible for errors and inaccuracies arising from data that might not be accurate.

Dated the 26th day of June, 2003.

William C. Yeomans

William C. Yeomans, B.Sc. (Hons.), P. Geo. (APEGBC)
(Association of Professional Engineers and Geoscientists of British Columbia)

