APPENDIX II
ASSAY CERTIFICATES

GEOLOGICAL SURVEY BRANCH
ASSESSMENT REPORT

27,385

3 of 3

4-Jul-03

ECO TECH LABORATORY LTD.
1004 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-216

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 30
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 1
Samples submitted by: TZ

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	13121	5	<0.2	3.32	<5	835	<5	1.11	<1	27	111	41	4.32	10	2.64	419	<1	0.06	72	1330	30	<5	<20	99	0.23	<10	113	<10	7	133
2	13122	85	0.5	1.28	15	245	<5	0.44	<1	6	44	44	1.40	<10	0.79	194	3	0.06	10	340	58	10	<20	82	0.04	<10	7	<10	8	193
3	13123	45	2.2	1.66	30	115	<5	0.62	11	6	56	156	1.92	<10	0.88	298	1	0.12	5	270	910	25	<20	65	0.04	<10	6	<10	6	2799
4	13124	50	2.2	1.71	25	105	<5	0.63	10	6	57	156	1.90	<10	0.86	275	2	0.12	5	260	770	30	<20	80	0.04	<10	7	<10	6	2620
5	13125	20	1.1	2.54	5	210	<5	1.00	9	12	75	174	1.87	<10	1.66	411	<1	0.15	45	340	942	35	<20	135	0.07	<10	28	<10	6	2213
6	13126	15	0.4	1.96	5	245	<5	1.45	<1	11	50	76	1.60	<10	1.48	425	3	0.10	33	140	104	35	<20	109	0.04	<10	13	<10	5	174
7	13127	95	1.5	2.74	255	45	<5	2.14	<1	35	361	350	5.86	10	3.00	625	1	0.05	247	610	70	70	<20	54	0.17	<10	58	<10	7	341
8	13128	130	2.0	0.47	20	15	<5	1.21	<1	7	86	118	4.65	10	0.41	151	13	<0.01	13	120	44	45	<20	10	0.07	<10	3	<10	4	120
9	13129	15	<0.2	0.31	<5	20	<5	0.35	1	9	75	13	5.87	10	0.28	27	5	<0.01	5	140	4	<5	<20	8	0.08	<10	2	<10	3	35
10	13130	35	0.6	0.22	<5	20	<5	0.28	<1	23	64	19	9.15	20	0.24	<1	9	<0.01	2	240	8	<5	<20	9	0.11	<10	1	<10	3	76
11	13131	25	0.2	0.24	<5	15	<5	0.30	<1	16	64	10	4.94	10	0.24	22	8	<0.01	3	160	6	<5	<20	13	0.06	<10	1	<10	2	76
12	13132	45	1.1	0.32	35	25	<5	0.33	<1	8	62	15	4.55	10	0.28	20	9	<0.01	4	190	8	<5	<20	11	0.06	<10	2	<10	3	41
13	13133	10	0.2	0.85	<5	60	<5	0.41	<1	4	64	4	2.33	<10	0.88	209	3	0.02	7	180	14	<5	<20	15	0.03	<10	3	<10	3	45
14	13134	15	0.3	0.80	<5	75	<5	0.24	<1	4	60	6	1.79	<10	0.92	199	5	<0.01	5	180	20	<5	<20	10	0.03	<10	2	<10	2	47
15	13135	50	1.4	1.12	40	55	<5	0.35	<1	9	38	16	3.14	10	1.20	242	3	0.02	7	230	42	5	<20	17	0.05	<10	3	<10	4	79
16	13136	170	3.1	0.35	90	10	<5	0.20	<1	20	84	64	6.02	10	0.22	<1	3	0.02	6	180	130	<5	<20	10	0.08	<10	4	<10	3	271
17	13137	65	0.9	0.27	25	5	<5	0.18	<1	42	125	14	9.35	20	0.21	<1	<1	<0.01	8	190	26	<5	<20	5	0.11	<10	3	<10	3	27
18	13138	60	0.7	0.24	15	10	<5	0.17	<1	38	97	11	8.88	20	0.20	<1	1	<0.01	6	200	20	<5	<20	5	0.11	<10	3	<10	3	25
19	13139	35	0.5	0.25	10	15	<5	0.23	<1	26	96	11	5.77	<10	0.19	3	<1	0.01	10	180	52	<5	<20	7	0.07	<10	5	<10	3	31
20	13140	20	0.2	4.52	<5	105	<5	0.77	<1	42	90	104	7.64	20	3.78	1242	<1	0.17	43	710	30	<5	<20	30	0.25	<10	252	10	6	228
21	13141	30	0.2	3.05	15	70	<5	0.90	<1	38	125	66	6.92	10	2.22	777	1	0.12	35	550	22	<5	<20	38	0.18	<10	110	<10	5	122
22	13142	<5	<0.2	1.97	<5	109	<5	1.73	<1	21	86	34	3.38	10	1.33	367	<1	0.20	32	764	19	<5	<20	94	0.20	<10	83	<10	9	48
23	13143	20	<0.2	4.99	<5	100	<5	2.42	<1	36	213	59	5.66	10	3.35	867	<1	0.33	99	1410	34	<5	<20	157	0.30	<10	204	<10	8	165
24	13144	30	0.6	0.91	30	10	<5	1.30	<1	40	61	79	9.48	20	0.64	181	<1	0.07	17	1230	32	15	<20	23	0.15	<10	51	<10	8	147
25	13145	<5	<0.2	2.13	<5	165	<5	2.11	<1	12	48	15	2.95	<10	1.39	833	<1	0.16	11	1580	28	<5	<20	42	0.12	<10	77	<10	3	108

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	13146	35	0.4	2.77	35	35	<5	0.91	1	44	66	46	>10	20	2.41	583	<1	0.07	17	1250	26	<5	<20	27	0.27	<10	121	<10	11	240
27	13147	125	0.4	2.50	40	35	<5	1.45	<1	44	58	52	9.14	20	1.92	523	<1	0.10	19	1050	36	5	<20	50	0.23	<10	108	<10	10	220
28	13148	35	0.5	2.20	30	25	<5	0.94	2	43	62	67	>10	20	1.77	579	<1	0.07	17	1020	58	<5	<20	37	0.27	<10	92	<10	12	356
29	13149	35	0.5	2.76	30	25	<5	0.79	<1	44	67	106	>10	20	2.33	752	<1	0.06	16	940	30	<5	<20	21	0.36	<10	119	<10	15	209
30	13150	30	0.3	1.25	<5	30	<5	0.96	<1	44	46	84	9.33	10	0.62	87	<1	0.06	14	1100	26	5	<20	20	0.22	<10	46	<10	11	72
QC DATA:																														
Resplit:																														
1	13121	5	<0.2	3.32	<5	870	<5	1.11	<1	29	111	41	4.41	10	2.58	450	<1	0.06	74	1340	30	<5	<20	100	0.23	<10	91	<10	9	135
Repeat:																														
1	13121	5	<0.2	3.34	<5	835	<5	1.12	<1	26	101	40	4.36	10	2.57	399	<1	0.06	69	1286	29	<5	<20	99	0.23	<10	91	<10	10	130
10	13130	35	0.6	0.24	<5	20	<5	0.28	<1	24	66	19	9.38	20	0.25	<1	9	<0.01	4	220	12	<5	<20	9	0.11	<10	1	<10	3	79
19	13139	35	0.5	0.27	<5	15	<5	0.24	<1	27	104	10	5.96	<10	0.19	6	<1	0.01	13	190	58	<5	<20	6	0.07	<10	6	<10	3	35
Standard:																														
GEO '03		125	1.6	1.65	65	160	<5	1.79	<1	22	71	86	3.70	10	0.97	675	<1	0.03	36	700	20	<5	<20	45	0.18	<10	72	<10	11	81

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
df/215
XLS/03

JUL 21 2003

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-226

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

10-Jul-03

ATTENTION: Bob Carmichael

No. of samples received: 40
Sample type: Core
Project #: Telsequah Chief
Shipment #: #2
Samples submitted by: TZ

ET #.	Tag #	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
2	13152	142	4.14	0.65	0.480	1.02

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

10-Jul-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-226

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 40
Sample type: Core
Project #: Telsequah Chief
Shipment #: #2
Samples submitted by: TZ

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	13151	70	0.8	0.72	30	15	<5	0.57	<1	36	46	84	>10	30	0.41	<1	<1	0.05	9	730	16	5	<20	23	0.02	<10	14	<10	6	327
2	13152	>1000	>30	1.21	550	55	<5	0.19	42	7	25	6301	3.34	<10	1.39	176	<1	0.04	6	470	4608	265	<20	12	<0.01	<10	3	<10	2	9909
3	13153	90	0.9	0.73	35	15	<5	0.58	<1	42	60	98	>10	30	0.47	<1	2	0.05	14	520	14	<5	<20	27	0.02	<10	24	<10	5	397
4	13154	60	0.4	0.45	30	15	<5	0.56	3	32	55	109	8.27	20	0.22	<1	<1	0.03	15	1140	10	5	<20	12	<0.01	<10	8	<10	6	1018
5	13155	60	0.9	0.49	15	20	<5	0.63	<1	36	74	89	8.08	20	0.21	<1	<1	0.04	19	1130	8	<5	<20	15	<0.01	<10	14	<10	7	45
6	13156	60	1.0	0.29	25	10	<5	0.41	2	24	75	516	6.62	10	0.21	<1	3	0.03	13	400	6	<5	<20	3	<0.01	<10	9	<10	4	317
7	13157	40	0.5	0.28	15	25	<5	0.29	<1	7	66	26	3.36	<10	0.14	50	3	0.03	2	390	4	<5	<20	4	<0.01	<10	<1	<10	5	20
8	13158	90	1.2	0.73	85	25	<5	0.53	<1	15	71	521	6.52	20	0.3	51	2	0.07	4	610	8	20	<20	16	0.02	<10	2	<10	6	25
9	13159	60	1.9	1.58	25	40	<5	1.07	<1	16	68	1368	4.83	10	0.56	269	2	0.17	9	740	12	40	<20	66	0.06	<10	24	<10	6	48
10	13160	15	0.2	4.91	5	250	<5	2.09	<1	31	121	66	5.36	10	2.73	1176	<1	0.24	55	810	18	<5	<20	100	0.15	<10	149	<10	7	107
11	13161	10	0.4	2.59	15	190	<5	1.21	3	20	178	81	3.78	<10	2.12	937	<1	0.19	52	690	74	25	<20	52	0.09	<10	117	<10	5	440
12	13162	35	0.3	2.97	10	140	<5	2.12	<1	37	178	82	4.03	<10	1.89	885	<1	0.29	47	760	22	10	<20	148	0.09	<10	91	<10	5	113
13	13163	10	0.3	3.9	5	340	<5	2.17	<1	19	202	66	3.96	10	2.42	929	<1	0.34	38	840	26	15	<20	162	0.12	<10	121	<10	6	102
14	13164	10	0.3	4.11	10	265	5	2.03	<1	33	193	77	4.68	10	2.96	998	<1	0.28	39	820	18	5	<20	109	0.12	<10	148	<10	6	108
15	13165	15	0.2	4.53	<5	215	<5	3.5	<1	32	213	102	4.87	10	2.35	1033	<1	0.39	77	660	16	<5	<20	210	0.12	<10	114	<10	5	94
16	13166	15	0.2	6.23	<5	485	10	3.13	<1	35	225	75	4.85	10	3.07	1039	<1	0.39	83	670	22	<5	<20	378	0.12	<10	151	<10	5	121
17	13167	10	<0.2	1.75	<5	125	<5	1.42	<1	20	81	40	3.22	10	1.15	319	4	0.18	31	850	20	<5	<20	82	0.13	<10	45	<10	8	48
18	13168	10	0.2	4.68	35	340	<5	3.18	<1	33	162	52	4.13	10	2.46	847	<1	0.37	86	1890	20	<5	<20	606	0.11	<10	114	<10	6	78
19	13169	10	0.3	5.05	35	235	<5	3.4	<1	33	286	67	5.04	10	2.97	936	<1	0.31	181	1560	32	10	<20	316	0.1	<10	117	<10	5	117
20	13170	20	0.7	4.49	55	110	<5	3.19	<1	70	186	155	6.34	20	2.09	652	<1	0.33	149	1390	38	15	<20	328	0.08	<10	88	<10	5	99
21	13171	15	<0.2	6.46	15	415	<5	3.54	<1	39	208	88	5.19	10	2.98	1096	<1	0.3	88	870	22	<5	<20	346	0.14	<10	197	<10	6	91
22	13172	20	0.2	5.82	10	405	<5	2.9	<1	32	173	94	5.39	10	2.72	968	<1	0.42	83	1880	22	<5	<20	426	0.13	<10	183	<10	7	88
23	13173	70	0.9	0.71	45	20	<5	0.43	<1	10	82	62	5.57	10	0.31	42	2	0.07	6	730	10	<5	<20	34	0.02	<10	<1	<10	7	21
24	13174	15	<0.2	4.83	<5	145	<5	3.36	<1	34	199	58	3.68	<10	1.81	951	<1	0.14	88	730	26	<5	<20	135	0.13	<10	80	<10	6	87
25	13175	25	0.2	0.72	15	40	<5	0.55	<1	10	73	28	3.26	<10	0.31	126	<1	0.04	14	190	8	<5	<20	46	0.01	<10	10	<10	3	19

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	13176	25	0.2	0.4	15	20	<5	0.2	<1	4	55	23	3.9	<10	0.17	20	<1	0.04	3	140	4	<5	<20	12	<0.01	<10	<1	<10	3	15
27	13177	55	0.7	0.27	25	10	<5	0.15	<1	6	65	32	4.68	<10	0.14	1	5	0.02	2	160	6	10	<20	5	<0.01	<10	<1	<10	3	51
28	13178	45	0.2	0.33	15	15	<5	0.21	<1	8	77	19	4.46	<10	0.16	4	3	0.03	4	140	6	<5	<20	10	<0.01	<10	<1	<10	4	16
29	13179	75	0.2	0.7	55	20	<5	0.57	<1	10	62	50	6.09	10	0.38	102	<1	0.06	6	270	12	<5	<20	74	<0.01	<10	5	<10	7	34
30	13180	20	<0.2	6.28	10	150	5	2.62	<1	39	79	55	6.67	20	2.91	1289	<1	0.18	36	970	28	<5	<20	530	0.16	<10	192	<10	8	126
31	13181	25	<0.2	5.46	20	130	<5	1.92	<1	39	78	80	6.38	10	3.06	1128	<1	0.19	38	910	24	<5	<20	288	0.13	<10	191	<10	7	117
32	13182	15	0.2	5.41	20	105	<5	1.9	<1	41	81	83	6.36	10	2.93	901	<1	0.22	42	980	26	<5	<20	143	0.12	<10	194	<10	7	100
33	13183	20	0.2	4.72	20	155	<5	1.59	<1	37	172	67	5.52	10	2.86	789	<1	0.27	65	800	26	10	<20	116	0.11	<10	182	<10	6	101
34	13184	30	0.2	5.03	20	60	<5	2.3	<1	29	199	80	5.63	10	2.34	1072	<1	0.26	68	370	24	<5	<20	86	0.11	<10	73	<10	6	220
35	13185	15	<0.2	3.08	15	45	<5	1.2	<1	14	102	28	4.74	<10	1.61	704	<1	0.13	30	210	18	5	<20	45	0.07	<10	23	<10	5	201
36	13186	10	<0.2	2.07	5	70	<5	0.97	<1	7	99	17	3.28	<10	1.03	427	2	0.17	20	370	14	5	<20	60	0.06	<10	<1	<10	6	123
37	13187	20	<0.2	0.96	15	35	<5	0.73	<1	5	77	17	3.41	<10	0.4	203	2	0.08	4	140	8	<5	<20	21	0.01	<10	<1	<10	4	225
38	13188	25	0.6	1.21	10	55	<5	2.58	<1	7	119	86	3.8	<10	0.54	661	3	0.09	14	200	34	25	<20	30	0.03	<10	5	<10	5	175
39	13189	15	<0.2	5.18	<5	265	<5	2.28	<1	39	88	65	6.57	10	3.27	1575	<1	0.37	41	1030	24	<5	<20	122	0.19	<10	198	<10	7	277
40	13190	15	0.6	3.77	45	100	<5	2.77	<1	38	160	131	5.29	<10	2.09	1291	<1	0.33	76	780	22	5	<20	169	0.12	<10	127	<10	5	139
QC DATA:																														
Resplit:																														
1	13151	65	0.8	0.76	25	5	<5	0.65	<1	35	51	84	9.35	20	0.4	<1	<1	0.05	9	790	24	10	<20	22	0.02	<10	15	<10	8	315
36	13186	10	<0.2	2.03	<5	70	<5	0.98	<1	7	112	17	3.23	<10	0.99	406	2	0.16	22	360	18	<5	<20	57	0.06	<10	<1	<10	6	129
Repeat:																														
1	13151	70	0.8	0.75	25	15	<5	0.59	<1	35	45	82	9.56	20	0.4	<1	<1	0.05	7	760	20	10	<20	20	0.03	<10	15	<10	7	332
2	13152	>1000	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
10	13160	15	0.2	5.09	5	245	<5	2.18	<1	32	126	65	5.57	10	2.81	1226	<1	0.25	55	840	20	<5	<20	102	0.15	<10	155	<10	7	113
19	13169	10	0.3	4.96	30	200	<5	3.37	<1	33	282	66	4.97	10	2.9	888	<1	0.3	181	1510	30	5	<20	313	0.09	<10	115	<10	5	117
36	13186	10	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Standard:																														
GEO '03		120	1.5	1.49	55	150	<5	1.63	<1	20	59	76	3.62	10	0.92	639	<1	0.02	31	730	22	<5	<20	37	0.08	<10	52	<10	10	81
GEO '03		120	1.6	1.54	65	145	<5	1.68	<1	20	60	77	3.69	10	0.94	644	<1	0.02	30	730	22	<5	<20	37	0.09	<10	53	<10	10	83

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
df/226
XLS/03

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
e-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-228

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

10-Jul-03

ATTENTION: Bob Carmichael

No. of samples received: 40
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 3
Samples submitted by: Redfern

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	13191			146	4.26	0.65	0.48	0.99
4	13194			318	9.27	1.48	10.0	14.8
28	13218			318	9.27	1.47	9.98	15.0
38	13228	2.12	0.062					

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

10-Jul-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-228

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 40
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 3
Samples submitted by: Redfern

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	13191	>1000	>30	1.48	635	30	<5	0.24	58	9	32	6203	4.08	10	1.64	246	<1	0.04	8	690	4680	315	<20	17	0.04	<10	4	<10	3	>10000
2	13192	10	1.1	4.49	50	245	<5	2.82	2	24	256	92	5.5	10	2.57	1356	7	0.41	110	790	38	25	<20	234	0.50	<10	132	<10	7	289
3	13193	30	1.0	0.6	20	60	<5	1.72	<1	9	85	263	3.52	<10	0.33	411	3	0.07	12	170	14	<5	<20	7	0.09	<10	7	<10	5	53
4	13194	>1000	>30	0.11	1920	5	<5	0.14	889	6	23	>10000	3.75	<10	0.12	47	<1	<0.01	<1	650	>10000	1160	<20	19	0.06	<10	4	<10	2	>10000
5	13195	55	1.8	0.26	50	20	<5	0.26	<1	10	96	159	5.76	10	0.15	47	1	0.03	6	170	35	<5	<20	4	0.03	<10	1	<10	6	136
6	13196	45	0.6	0.19	35	30	<5	0.39	<1	6	83	409	3.64	<10	0.13	140	<1	0.02	4	160	20	10	<20	2	0.03	<10	<1	<10	7	192
7	13197	25	0.4	0.53	25	40	<5	0.32	1	10	78	509	3.88	<10	0.33	212	2	0.03	4	330	12	<5	<20	15	0.06	<10	3	<10	7	284
8	13198	20	0.2	3.35	15	80	<5	0.88	<1	26	65	50	6.75	10	2.85	1023	3	0.04	13	1270	8	<5	<20	46	0.28	<10	31	<10	13	116
9	13199	20	<0.2	3.52	25	60	<5	0.84	<1	27	66	12	7.05	20	2.92	872	4	0.05	13	1400	6	<5	<20	46	0.19	<10	36	<10	11	113
10	13200	20	0.2	3.23	25	60	<5	0.89	<1	26	72	21	6.89	10	2.64	887	4	0.04	15	1340	12	<5	<20	37	0.18	<10	18	<10	16	198
11	13201	40	0.2	2.78	50	45	<5	0.85	<1	27	60	119	7.16	10	2.03	697	1	0.04	10	930	14	<5	<20	32	0.22	<10	45	<10	13	95
12	13202	60	0.5	2.39	60	50	<5	0.8	<1	29	54	629	6.69	10	1.61	521	3	0.06	9	1020	12	5	<20	26	0.23	<10	46	<10	11	82
13	13203	55	0.2	3.39	50	35	<5	1	<1	33	84	144	9.61	20	2.51	668	<1	0.06	14	680	14	<5	<20	40	0.19	<10	80	<10	10	86
14	13204	15	<0.2	3.83	15	60	<5	1.17	<1	31	76	55	8.1	20	2.84	792	2	0.06	15	710	16	<5	<20	71	0.22	<10	85	<10	12	103
15	13205	40	<0.2	4.53	40	45	<5	1.26	<1	35	62	23	8.67	20	3.06	785	<1	0.09	15	750	16	<5	<20	61	0.25	<10	109	<10	11	91
16	13206	20	<0.2	3.32	30	30	<5	0.64	<1	35	69	124	>10	20	2.65	686	<1	0.04	14	670	14	<5	<20	23	0.19	<10	73	<10	11	97
17	13207	10	<0.2	3.44	20	50	<5	0.56	<1	29	54	106	8.12	20	2.57	752	<1	0.05	13	660	16	5	<20	30	0.16	<10	79	<10	8	99
18	13208	10	<0.2	4.09	20	70	<5	0.63	<1	27	95	14	8.08	20	2.94	995	<1	0.06	14	630	14	<5	<20	33	0.19	<10	95	<10	8	115
19	13209	15	<0.2	3.48	35	60	<5	0.54	<1	27	78	34	7.4	10	2.51	826	2	0.06	12	720	12	10	<20	22	0.20	<10	88	<10	8	95
20	13210	35	<0.2	3.35	45	60	<5	0.73	<1	30	74	22	7.6	20	2.4	894	<1	0.06	14	820	10	<5	<20	31	0.17	<10	87	<10	10	86
21	13211	75	<0.2	3.8	90	50	<5	0.95	<1	30	83	25	8.9	20	2.64	1119	2	0.07	13	800	20	<5	<20	42	0.22	<10	94	<10	11	103
22	13212	10	0.2	2.13	<5	150	<5	2.04	<1	29	109	22	4.13	10	1.33	429	6	0.21	39	1030	14	<5	<20	101	0.31	<10	43	<10	11	55
23	13213	30	0.2	3.01	50	55	<5	0.62	<1	28	78	133	7.8	20	2.06	831	2	0.05	10	770	16	<5	<20	41	0.25	<10	72	<10	9	85
24	13214	40	0.4	2.06	50	50	<5	0.91	<1	26	75	280	7.07	10	1.35	739	2	0.04	10	780	88	50	<20	23	0.21	<10	54	<10	9	176
25	13215	25	0.2	3.74	50	60	<5	0.87	<1	36	55	182	8.84	20	2.92	1191	<1	0.04	15	740	16	<5	<20	39	0.25	<10	119	<10	10	104

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	13216	15	<0.2	3.43	35	55	<5	0.62	<1	32	58	221	8.49	20	2.38	931	<1	0.06	12	740	16	<5	<20	30	0.29	<10	94	<10	9	70
27	13217	20	0.2	3.75	35	65	<5	0.64	<1	34	58	450	8.82	20	2.61	1159	<1	0.05	13	760	20	<5	<20	23	0.26	<10	93	<10	10	81
28	13218	>1000	>30	0.12	2145	15	<5	0.14	943	6	24	>10000	3.82	<10	0.12	52	<1	<0.01	<1	690	>10000	1270	<20	21	0.06	<10	4	<10	2	>10000
29	13219	20	0.4	3.97	35	65	<5	0.68	<1	36	55	476	9.24	20	2.92	1321	<1	0.05	13	770	38	<5	<20	23	0.31	<10	90	<10	10	134
30	13220	15	0.2	3.07	30	50	<5	0.7	<1	30	60	65	8.07	20	2.22	785	<1	0.05	11	770	16	<5	<20	21	0.26	<10	65	<10	12	63
31	13221	15	0.2	4.25	15	50	<5	0.69	<1	30	65	427	9.74	20	3.36	1460	<1	0.06	15	700	14	<5	<20	18	0.24	<10	97	<10	11	98
32	13222	15	0.3	4.69	35	80	<5	0.79	<1	34	64	338	8.9	20	3.53	1460	1	0.1	17	800	16	<5	<20	19	0.32	<10	119	<10	10	99
33	13223	20	0.5	4.45	35	65	<5	0.7	<1	35	69	675	8	20	3.29	1265	1	0.14	14	770	16	<5	<20	8	0.30	<10	124	<10	8	120
34	13224	15	0.4	4.36	30	70	<5	0.64	<1	36	63	689	8.18	20	3.37	1262	<1	0.12	15	810	20	<5	<20	6	0.25	<10	123	<10	9	118
35	13225	20	<0.2	3.96	50	60	<5	0.61	<1	35	57	156	8.12	20	2.95	1083	<1	0.12	13	790	8	<5	<20	6	0.23	<10	114	<10	9	99
36	13226	10	0.2	3.88	45	60	<5	0.59	<1	32	67	246	7.52	20	2.65	898	<1	0.12	13	810	14	<5	<20	7	0.20	<10	117	<10	9	89
37	13227	15	0.1	4.22	35	105	<5	0.66	<1	34	63	52	7.22	20	3.02	883	<1	0.12	16	780	16	5	<20	14	0.20	<10	144	<10	9	95
38	13228	>1000	8.5	0.35	145	25	<5	0.2	8	14	45	328	5.09	10	0.21	<1	8	0.02	6	50	14	10	<20	<1	0.03	<10	<1	<10	4	2056
39	13229	40	0.3	4.01	90	30	<5	0.67	<1	38	72	18	>10	20	3.22	742	<1	0.11	13	860	18	<5	<20	9	0.30	<10	118	<10	10	84
40	13230	80	1.7	2.09	90	50	<5	0.87	2	34	155	127	5.36	10	1.85	318	3	0.12	68	530	56	10	<20	34	0.13	<10	56	<10	7	379
QC DATA:																														
Resplit:																														
36	13226	15	0.3	4.01	50	65	<5	0.62	<1	33	70	248	7.79	20	2.73	937	<1	0.12	14	840	14	<5	<20	7	0.21	<10	111	<10	10	92
Repeat:																														
1	13191	>1000	>30	1.39	615	25	<5	0.24	56	9	31	5987	3.97	<10	1.59	239	<1	0.03	7	710	4658	315	<20	15	0.05	<10	4	<10	3	>10000
4	13194	>1000	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
10	13200	20	<0.2	3.24	20	60	<5	0.89	<1	25	72	18	6.92	20	2.65	879	1	0.04	13	1370	14	<5	<20	37	0.18	<10	19	<10	16	195
19	13209	15	<0.2	3.35	35	55	<5	0.53	<1	27	75	34	7.25	10	2.44	795	5	0.06	13	690	14	10	<20	21	0.18	<10	83	<10	8	93
28	13218	-	>30	0.11	2089	20	<5	0.14	926	6	24	>10000	4.18	<10	0.12	45	<1	<0.01	<1	650	>10000	1110	<20	17	0.06	<10	4	<10	2	>10000
36	13226	20	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Standard:																														
GEO '03		120	1.6	1.68	60	150	<5	1.86	<1	20	60	86	3.85	20	0.92	698	1	0.02	30	800	24	5	<20	45	0.11	<10	73	<10	12	74
GEO '03		120	1.6	1.71	65	145	<5	2.02	<1	20	60	87	3.85	20	0.94	749	<1	0.02	30	890	26	5	<20	46	0.11	<10	72	<10	13	75

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
df/218
XLS/03

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-229

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

10-Jul-03

ATTENTION: Bob Carmichael

No. of samples received: 25
Sample type: Rock
Project #:Tulsequah Chief
Shipment #: 4
Samples submitted by: TZ

ET #.	Tag #	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
2	13232	144	4.20	0.64	0.47	0.99

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

10-Jul-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-229

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 25
Sample type: Rock
Project #:Tulsequah Chief
Shipment #: 4
Samples submitted by: TZ

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	13231	295	10.9	0.33	230	30	<5	0.26	20	13	44	465	4.95	<10	0.17	<1	4	0.02	5	110	1569	<5	<20	1	0.02	<10	<1	<10	5	3415
2	13232	90	5.9	0.98	60	65	<5	1.23	10	10	45	210	4	<10	0.57	134	6	0.06	10	80	890	<5	<20	15	0.02	<10	3	<10	6	1896
3	13233	120	5.7	1.56	35	65	<5	1.84	38	21	87	715	5.47	<10	0.75	223	13	0.13	29	260	650	<5	<20	83	0.04	<10	19	<10	5	6575
4	13234	10	<0.2	1.63	<5	160	<5	0.79	<1	7	77	6	1.67	<10	0.87	209	2	0.15	7	270	8	<5	<20	26	0.06	<10	<1	<10	7	47
5	13235	<5	<0.2	1.97	<5	60	<5	1.32	<1	6	65	15	1.77	<10	0.63	231	4	0.24	7	300	10	<5	<20	37	0.10	<10	<1	<10	6	43
6	13236	10	<0.2	1.25	<5	60	<5	1.12	<1	8	67	10	1.59	<10	0.44	224	2	0.14	7	280	12	<5	<20	35	0.06	<10	<1	<10	6	38
7	13237	10	<0.2	0.9	<5	85	<5	1.32	<1	5	64	13	1.23	<10	0.37	315	2	0.08	7	260	10	<5	<20	20	0.02	<10	<1	<10	6	35
8	13238	15	<0.2	0.88	<5	75	<5	1.2	<1	9	61	15	1.55	<10	0.36	251	2	0.08	6	260	22	<5	<20	18	0.02	<10	<1	<10	6	33
9	13239	10	0.2	0.98	<5	75	<5	2.21	4	10	55	24	1.92	<10	0.6	542	<1	0.05	23	310	70	<5	<20	46	0.01	<10	8	<10	8	146
10	13240	5	<0.2	1.84	<5	100	<5	1.71	<1	8	73	20	1.65	<10	0.7	443	2	0.12	28	450	16	<5	<20	76	0.05	<10	7	<10	7	40
11	13241	<5	<0.2	1.4	<5	90	<5	1.37	<1	3	58	12	1.03	<10	0.34	442	<1	0.07	7	220	8	5	<20	33	0.02	<10	<1	<10	4	22
12	13242	<5	<0.2	1.97	<5	125	<5	1.81	<1	23	108	29	3.85	10	1.19	400	7	0.21	37	980	16	<5	<20	95	0.18	<10	35	<10	11	35
13	13243	10	0.5	2.08	25	95	<5	2.14	<1	9	83	32	1.86	<10	0.28	995	6	0.08	10	310	48	<5	<20	24	0.04	<10	3	<10	5	43
14	13244	260	11.8	0.27	265	10	<5	0.52	<1	63	92	168	8.36	10	0.12	202	<1	0.02	44	250	759	<5	<20	<1	0.02	<10	6	<10	6	1070
15	13245	250	22.6	0.46	320	5	<5	0.5	<1	50	95	426	>10	20	0.27	213	<1	0.03	20	160	503	<5	<20	<1	0.03	<10	16	<10	6	960
16	13246	80	3.7	3.25	60	180	<5	1.28	5	29	63	168	5.41	<10	1.41	2065	<1	0.12	12	670	1059	<5	<20	25	0.12	<10	83	<10	9	1430
17	13247	35	0.7	3.03	35	200	<5	0.83	<1	37	226	85	5.22	<10	2.78	1469	2	0.09	193	760	138	<5	<20	34	0.12	<10	67	<10	7	370
18	13248	5	0.2	3.36	25	2005	5	1.63	<1	50	539	61	3.62	<10	4.79	623	3	0.06	479	1330	22	5	<20	157	0.13	<10	46	<10	6	182
19	13249	20	0.8	4.43	15	95	<5	0.69	9	52	167	520	7.24	10	4.06	1269	<1	0.09	75	760	18	10	<20	56	0.11	<10	155	<10	9	1950
20	13250	25	2.0	4.96	20	80	<5	1.64	47	49	79	1325	9.81	20	4.47	1752	<1	0.09	29	1170	24	<5	<20	16	0.09	<10	191	<10	10	7589
21	13251	40	0.5	4.9	10	255	<5	2.01	<1	36	95	105	7.9	10	3.04	1298	<1	0.25	29	910	32	10	<20	72	0.16	<10	186	<10	10	168
22	13252	>1000	>30	1.39	600	35	<5	0.23	55	9	30	6103	3.96	<10	1.62	236	<1	0.03	8	690	4652	320	<20	17	0.03	<10	4	<10	3	9780
23	13253	50	2.5	4.57	40	120	<5	1.92	18	37	169	223	6.76	10	3.46	2162	<1	0.17	93	1180	112	20	<20	111	0.13	<10	128	<10	9	3638
24	13254	10	0.7	3.22	10	220	<5	5.08	<1	27	159	44	3.32	<10	1.9	1504	3	0.27	103	1260	90	<5	<20	270	0.15	<10	62	<10	6	130
25	13255	15	0.6	5.08	60	60	<5	1.1	9	50	128	148	8.46	20	4.27	2550	4	0.12	44	770	50	10	<20	61	0.20	<10	162	<10	9	2240

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC DATA:																														
Resplit:																														
1	13231	320	10.9	0.31	240	20	<5	0.27	19	14	45	462	5.14	<10	0.18	<1	5	0.01	3	130	1570	<5	<20	<1	0.02	<10	<1	<10	6	3420
Repeat:																														
1	13231	305	11.2	0.35	260	25	<5	0.29	23	14	49	458	5.54	10	0.19	<1	4	0.02	3	130	1576	<5	<20	<1	0.02	<10	<1	<10	6	3399
10	13240	5	<0.2	1.86	<5	105	<5	1.72	<1	8	74	20	1.66	<10	0.72	435	2	0.11	30	460	14	<5	<20	75	0.04	<10	11	<10	7	42
19	13249	25	0.8	4.34	15	65	<5	0.68	9	53	165	518	7.2	10	3.99	1250	2	0.09	76	740	20	<5	<20	54	0.11	<10	153	<10	8	1923
Standard:																														
GEO '03		120	1.6	1.55	60	160	<5	1.83	<1	25	68	87	4.13	10	0.91	693	2	0.02	36	870	24	5	<20	45	0.11	<10	72	<10	12	73

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
df/218
XLS/03

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-0238

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

15-Jul-03

ATTENTION: **Bob Carmichael**

No. of samples received: 26
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 5
Samples Submitted by: T.Z.

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
19	13274	1.17	0.034	18.6	0.54	0.34	1.00	5.08
20	13275	-	-	9.1	0.27	0.20	0.01	1.80
22	13277	1.26	0.037	20.6	0.60	0.79	0.11	6.44
23	13278	1.29	0.038	-	-	-	-	-
24	13279	2.70	0.079	34.2	1.00	0.57	0.07	0.68
QC DATA:								
Standard:								
PM168		2.08	0.061	-	-		-	-
Cu106		-	-	138.0	4.02		-	-
MP1a		-	-	70.00	2.04		4.30	19.1

JJ/ejd
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

14-Jul-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-238

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 26
Sample type: Rock
Project #: Tulsequah Chief
Shipment #: 5
Samples submitted by: TZ

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	13256	90	1.6	5.88	70	<5	<5	0.75	27	41	134	140	9.39	<10	5.19	3871	2	0.09	32	810	46	<5	20	36	0.16	<10	227	<10	12	7250
2	13257	65	1.6	5.22	110	10	<5	2.37	5	40	91	151	6.8	<10	2.08	3216	12	0.09	23	940	668	<5	<20	23	0.25	<10	192	<10	11	1632
3	13258	35	2.0	4.02	30	15	<5	1.66	19	47	90	283	7.5	<10	2.17	2439	6	0.04	21	760	584	<5	<20	13	0.18	<10	154	<10	10	4364
4	13259	35	2.5	2.51	20	15	<5	0.55	6	44	82	332	6.17	<10	1.31	1456	6	0.02	23	750	582	25	<20	5	0.15	<10	82	<10	9	1730
5	13260	170	9.8	0.63	30	10	<5	0.81	15	8	68	463	2.79	<10	0.45	135	2	0.03	5	170	506	10	<20	31	<0.01	<10	3	<10	5	3139
6	13261	75	3.0	3.1	20	15	<5	1.79	14	19	171	193	3.66	<10	3.03	737	5	0.12	76	1280	330	<5	<20	183	0.07	<10	56	<10	6	2808
7	13262	160	6.6	0.75	130	<5	<5	0.87	5	10	100	809	5.56	<10	0.51	150	3	0.05	11	250	586	35	<20	31	<0.01	<10	4	<10	4	1407
8	13263	40	1.0	0.44	5	10	<5	0.48	<1	4	110	144	2.6	<10	0.28	100	7	0.02	3	230	32	<5	<20	16	<0.01	<10	3	<10	3	58
9	13264	95	2.0	0.27	50	<5	<5	0.23	<1	8	112	18	5.68	<10	0.15	<1	4	0.01	3	220	54	<5	<20	10	<0.01	<10	1	<10	3	46
10	13265	180	0.8	0.23	160	<5	<5	0.18	<1	6	77	19	5.66	<10	0.11	<1	6	0.01	1	320	32	<5	<20	7	<0.01	<10	1	<10	4	22
11	13266	595	1.1	0.22	110	<5	<5	0.15	<1	16	102	183	4.63	<10	0.1	<1	5	0.01	8	70	44	10	<20	7	<0.01	<10	<1	<10	3	37
12	13267	<5	<0.2	2.05	<5	130	<5	1.49	<1	23	85	36	3.34	10	1.19	332	10	0.25	29	830	18	<5	<20	113	0.18	<10	50	<10	9	44
13	13268	200	0.8	0.23	75	5	<5	0.33	<1	10	84	272	3.04	<10	0.11	52	5	0.01	5	120	36	<5	<20	9	<0.01	<10	4	<10	2	23
14	13269	435	0.8	0.24	90	<5	<5	0.25	<1	11	92	36	5.31	<10	0.14	<1	4	0.01	4	160	72	<5	<20	7	<0.01	<10	1	<10	3	53
15	13270	205	1.0	0.22	75	<5	<5	0.23	<1	10	83	27	4.45	<10	0.13	<1	3	<0.01	3	150	56	<5	<20	5	<0.01	<10	1	<10	3	43
16	13271	150	1.6	0.28	110	<5	<5	0.23	<1	7	77	39	3.4	<10	0.12	<1	<1	0.01	3	230	52	<5	<20	6	<0.01	<10	<1	<10	3	52
17	13272	210	2.4	0.22	140	<5	<5	0.15	<1	5	102	83	3.79	<10	0.09	<1	2	<0.01	3	150	70	5	<20	4	<0.01	<10	<1	<10	3	106
18	13273	135	1.0	0.27	130	<5	<5	0.23	<1	6	73	34	3.36	<10	0.13	5	2	<0.01	3	240	56	<5	<20	6	<0.01	<10	<1	<10	3	55
19	13274	>1000	18.1	0.4	725	<5	<5	0.95	199	7	50	3020	3.92	<10	0.15	114	<1	0.03	<1	370	>10000	40	<20	20	0.00	<10	3	<10	3	>10000
20	13275	240	8.9	0.77	375	<5	<5	0.72	71	11	41	1864	5.89	<10	0.24	3	<1	0.06	3	1660	84	40	<20	13	0.01	<10	<1	<10	7	>10000
21	13276	795	18.2	0.32	675	<5	<5	0.27	6	15	65	3890	>10	<10	0.25	<1	<1	0.02	5	630	182	5	<20	5	0.01	<10	4	<10	6	3287
22	13277	>1000	20.5	0.19	385	<5	<5	0.12	251	8	75	7850	>10	<10	0.22	<1	<1	0.01	<1	240	900	<5	<20	4	0.00	<10	4	<10	5	>10000
23	13278	>1000	16.6	0.14	125	<5	<5	0.13	8	9	126	9353	>10	<10	0.22	<1	<1	0.01	3	340	284	<5	<20	3	0.00	<10	4	<10	5	3020
24	13279	>1000	>30	1.22	245	<5	<5	1.02	21	15	117	5456	>10	10	0.96	155	<1	0.11	19	500	620	30	<20	19	0.05	<10	29	<10	5	6428
25	13280	85	1.1	1.88	25	10	<5	0.92	2	10	79	105	3.84	<10	1.28	646	4	0.12	17	490	388	<5	<20	23	0.04	<10	23	<10	6	594
26	13281	50	0.2	1.92	45	15	<5	0.51	<1	7	88	18	3.15	<10	1.81	939	4	0.06	8	230	28	<5	<20	17	0.03	<10	<1	<10	7	116

REDFERN RESOURCES LTD. - AK3-238

14-Jul-03

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC DATA:																														
Resplit:																														
1	13256	95	1.4	5.88	90	<5	<5	0.73	25	40	137	139	9.5	<10	5.24	3868	2	0.08	33	760	42	<5	<20	36	0.16	<10	221	<10	11	7099
Repeat:																														
1	13256	95	1.5	5.9	85	<5	<5	0.73	26	39	132	139	9.3	<10	5.25	3888	4	0.08	34	790	40	<5	<20	35	0.17	<10	223	<10	11	7276
10	13265	180	0.8	0.24	160	<5	<5	0.18	<1	6	78	19	5.67	<10	0.11	<1	7	0.01	2	310	30	<5	<20	7	<0.01	<10	1	<10	4	22
11	13266	570																												
14	13269	480																												
21	13276	810																												
Standard:																														
GEO '03		125	1.6	1.76	55	150	<5	1.75	<1	23	66	89	3.82	<10	1.03	667	4	0.04	31	690	24	<5	<20	52	0.11	<10	68	<10	12	75

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/ejd
df/227
XLS/03

Eco Tech Laboratory Ltd.

JUL 21 2003

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-239

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

14-Jul-03

ATTENTION: Bob Carmichael

No. of samples received: 25
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 6
Samples Submitted by: T.Z

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
3	13284	2.34	0.068	37.5	1.09	2.02	0.07	0.49
4	13285	4.53	0.132	38.4	1.12	0.49	0.04	0.02
6	13287	1.47	0.043	-	-	-	-	
7	13288	1.50	0.044	10.3	0.30	1.45	0.02	2.16
8	13289	-	-	3.6	0.11	1.25	<0.01	0.74
9	13290	1.14	0.033	11.4	0.33	1.85	0.05	0.36
10	13291a	-	-	142.0	4.14	0.63	0.46	0.96
10	13291b	2.08	0.061	-	-	-	-	-
11	13292	-	-	8.6	0.25	2.06	0.11	0.57
12	13293	1.08	0.031	7.5	0.22	2.47	0.05	0.18
13	13294b	2.06	0.060	-	-	-	-	-
20	13301	1.44	0.042	-	-	-	-	-
22	13303	1.68	0.049	-	-	-	-	-
23	13304	1.08	0.031	-	-	-	-	-

QC DATA:

Standard:

PM168	2.08	0.061	-	-	-	-	-
MP1a	-	-	69.70	2.03	1.44	4.3	19.10
Cu 106	-	-	138.00	-	1.43	-	-

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/ejd
XLS/03

14-Jul-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-239

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 25
Sample type: Core
Project #:Tulsequah Chief
Shipment #: 6
Samples submitted by: TZ

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	13282	250	1.7	0.66	25	<5	<5	0.53	1	12	84	525	6.34	<10	0.45	94	3	0.02	7	230	134	<5	<20	23	<0.01	<10	9	<10	4	705
2	13283	540	1.8	0.38	50	<5	<5	0.33	<1	7	48	529	3.82	<10	0.15	<1	2	0.02	6	450	148	<5	<20	23	<0.01	<10	3	<10	3	297
3	13284	>1000	>30	0.1	635	<5	<5	0.09	11	14	102	>10000	>10	<10	0.24	<1	<1	<0.01	2	780	686	25	<20	<1	0.01	<10	6	<10	4	4512
4	13285	>1000	>30	0.17	865	<5	<5	0.17	<1	19	92	4870	>10	<10	0.25	<1	<1	<0.01	8	140	380	30	<20	5	<0.01	<10	10	<10	5	192
5	13286	650	7.7	0.23	865	<5	<5	0.12	<1	25	97	2340	9.5	<10	0.17	<1	11	<0.01	12	80	124	55	<20	7	<0.01	<10	11	<10	3	442
6	13287	>1000	11.2	0.23	400	<5	<5	0.83	<1	15	77	1129	>10	<10	0.37	<1	<1	<0.01	10	60	394	40	<20	10	<0.01	<10	19	<10	5	1068
7	13288	>1000	10	0.35	460	<5	<5	0.54	87	11	82	>10000	>10	<10	0.4	<1	<1	0.01	4	740	190	<5	<20	9	0.01	<10	8	<10	6	>10000
8	13289	400	3.4	2.28	45	<5	<5	2.42	35	24	91	>10000	6.1	<10	1.68	290	7	0.21	35	1920	42	<5	<20	57	0.13	<10	66	<10	10	7289
9	13290	>1000	11	0.21	480	<5	<5	0.23	7	10	113	>10000	>10	<10	0.3	<1	<1	0.01	4	1000	412	30	<20	2	0.01	<10	9	<10	5	3292
10	13291	>1000	>30	1.64	605	<5	<5	0.21	42	7	28	6470	3.56	<10	1.8	231	<1	0.05	7	580	4332	175	<20	19	0.01	<10	5	<10	3	9376
11	13292	940	8.3	0.14	300	<5	<5	0.05	16	11	94	>10000	>10	<10	0.23	<1	<1	<0.01	1	770	989	<5	<20	3	0.01	<10	6	<10	5	5578
12	13293	>1000	7.1	0.16	335	<5	<5	0.08	14	14	104	>10000	>10	<10	0.29	<1	17	<0.01	44	920	362	135	<20	3	0.01	<10	10	<10	5	1678
13	13294	>1000	>30	0.13	1815	<5	<5	0.14	899	5	21	>10000	4.02	<10	0.15	46	<1	<0.01	<1	680	>10000	1120	<20	20	0.01	<10	6	<10	2	>10000
14	13295	245	3.6	0.41	170	<5	<5	0.38	<1	54	64	415	>10	<10	0.34	<1	<1	0.03	18	410	56	<5	<20	11	<0.01	<10	21	<10	6	948
15	13296	45	0.3	4.58	25	20	<5	3.11	<1	41	156	118	5.61	<10	2.59	311	10	0.54	93	1540	20	<5	<20	215	0.21	<10	83	<10	9	131
16	13297	130	1.1	3.53	70	<5	<5	2.32	<1	44	129	1378	8.41	<10	2.04	269	7	0.41	78	1240	18	<5	<20	126	0.15	<10	79	<10	8	451
17	13298	35	0.4	5.54	15	595	<5	3.6	<1	31	324	596	3.97	<10	4.63	1373	5	0.28	176	1450	14	<5	<20	77	0.14	<10	155	<10	7	232
18	13299	230	1.8	0.55	195	<5	<5	0.38	<1	33	68	158	>10	<10	0.41	<1	<1	0.04	14	400	56	<5	<20	9	0.01	<10	16	<10	8	109
19	13300	80	1.1	0.76	75	<5	<5	0.37	<1	26	106	100	5.73	<10	0.21	<1	<1	0.05	12	470	20	<5	<20	8	0.01	<10	26	<10	6	147
20	13301	>1000	3.1	0.33	490	<5	<5	0.34	<1	27	74	48	>10	<10	0.26	<1	<1	0.03	6	510	104	<5	<20	7	<0.01	<10	11	<10	7	114
21	13302	195	1.3	0.51	115	<5	<5	0.41	<1	25	62	58	5.8	<10	0.18	<1	<1	0.05	9	550	18	<5	<20	10	0.01	<10	13	<10	6	99
22	13303	>1000	2.8	0.38	525	<5	<5	0.49	<1	24	84	126	>10	<10	0.29	<1	<1	0.02	5	1060	86	<5	<20	8	0.01	<10	11	<10	9	136
23	13304	>1000	2.9	0.4	415	<5	<5	0.47	<1	23	69	78	>10	10	0.29	<1	<1	0.02	4	1000	76	<5	<20	10	<0.01	<10	6	<10	9	59
24	13305	70	0.2	3.5	50	<5	<5	1.17	<1	12	73	52	>10	10	4.26	1418	<1	0.01	14	1300	8	<5	<20	17	0.00	<10	6	<10	12	157
25	13306	90	0.3	4.15	50	<5	<5	0.7	<1	16	72	78	>10	10	5.1	1611	<1	0.01	16	1290	8	<5	<20	15	0.01	<10	5	<10	11	217

REDFERN RESOURCES LTD. - AK3-239

14-Jul-03

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC DATA:																														
Resplit:																														
1	13282	250	1.5	0.69	30	<5	<5	0.61	2	13	91	513	6.37	<10	0.48	122	2	0.02	9	250	150	<5	<20	22	<0.01	<10	10	<10	4	704
Repeat:																														
1	13282	240	1.7	0.67	30	<5	<5	0.54	1	13	85	528	6.42	<10	0.45	98	3	0.02	8	230	138	<5	<20	23	<0.01	<10	9	<10	4	703
2	13283	600																												
5	13286	660																												
10	13291	>1000	>30	1.66	610	<5	<5	0.21	42	7	29	6356	3.6	<10	1.79	231	<1	0.05	7	670	4330	185	<20	20	0.01	<10	5	<10	3	9462
11	13292	890																												
Standard:																														
GEO '03		125	1.6	1.77	60	145	<5	1.68	<1	21	63	92	3.71	<10	1	643	2	0.02	31	650	22	<5	<20	49	0.11	<10	69	<10	10	73

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
df
XLS/03

Eco Tech Laboratory Ltd.

AUG 4 2003

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-247

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

25-Jul-03

ATTENTION: Bob Carmichael

No. of samples received: 27
Sample type: Core
Project #: Tulsequah Chief
Shipment #: #9
Samples submitted by: TZ

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	13358	<0.03	<0.001					
2	13359	0.12	0.003					
3	13360	0.08	0.002					
4	13361	<0.03	<0.001					
5	13362	0.08	0.002					
6	13363	0.88	0.026	64.0	1.87	0.23	1.68	2.80
7	13364	1.22	0.036	40.0	1.17	0.25	1.03	2.20
8	13365	1.57	0.046					
9	13366	0.16	0.005					
10	13367	<0.03	<0.001					
11	13368	0.03	0.001					
12	13369	0.26	0.008					
13	13370	0.26	0.008					
14	13371	0.14	0.004					
15	13372	0.07	0.002					
16	13373	<0.03	<0.001					
17	13374	0.10	0.003					
18	13375	<0.03	<0.001					
19	13376	0.13	0.004					
20	13377	<0.03	<0.001					
21	13378	0.05	0.001					
22	13379	0.05	0.001					
23	13380	0.04	0.001					
24	13381	0.10	0.003					
25	13382	0.08	0.002					
26	13383	0.08	0.002					
27	13384	0.04	0.001					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. AK3-247 25-Jul-03

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
QC DATA:								
Repeat:								
1	13358	<0.03	<0.001					
10	13367	<0.03	<0.001					
19	13376	0.11	0.003					
Resplit:								
1	13358	<0.03	<0.001					
Standard:								
PM168		2.06	0.060					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
XLS/03

25-Jul-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-247

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 27
Sample type: Core
Project #: Tulsequah Chief
Shipment #: #9
Samples submitted by: TZ

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	13358	0.5	0.36	10	130	<5	2.20	<1	3	54	55	1.30	<10	0.51	465	<1	<0.01	8	140	44	25	<20	47	<0.01	<10	4	<10	5	103
2	13359	0.7	0.15	45	<5	<5	0.23	<1	8	97	161	>10	10	0.22	<1	25	<0.01	2	60	52	30	<20	10	0.01	<10	1	<10	4	435
3	13360	7.4	0.18	80	<5	<5	0.29	16	7	67	374	4.01	<10	0.10	24	8	<0.01	8	130	742	190	<20	9	<0.01	<10	1	<10	2	4175
4	13361	0.1	0.34	<5	135	<5	0.69	<1	2	52	37	0.78	<10	0.28	151	<1	<0.01	4	200	72	10	<20	63	<0.01	<10	1	<10	4	318
5	13362	0.9	1.03	5	105	<5	1.38	1	7	76	98	1.72	<10	0.91	399	1	0.05	33	250	74	<5	<20	87	0.03	<10	9	<10	5	462
6	13363	>30	0.21	110	<5	<5	0.72	112	6	41	2181	3.37	<10	0.35	68	3	0.01	<1	300	>10000	460	<20	64	<0.01	<10	<1	<10	3	>10000
7	13364	>30	0.15	380	<5	<5	0.58	83	7	30	2395	3.71	<10	0.22	41	<1	<0.01	2	260	>10000	395	<20	69	<0.01	<10	<1	<10	3	>10000
8	13365	10.9	0.25	160	<5	<5	0.43	17	5	33	661	3.40	<10	0.07	19	<1	<0.01	<1	110	1744	305	<20	99	<0.01	<10	<1	<10	2	4409
9	13366	7.2	0.23	45	<5	<5	0.41	3	8	62	368	5.00	<10	0.20	47	10	<0.01	2	220	112	145	<20	43	<0.01	<10	<1	<10	4	899
10	13367	0.2	2.02	<5	190	<5	1.54	<1	17	96	52	3.18	<10	1.25	340	11	0.22	33	780	24	<5	<20	108	0.20	<10	50	<10	7	58
11	13368	0.6	1.39	15	<5	<5	2.15	<1	15	59	20	9.97	<10	2.59	340	4	0.01	12	340	20	<5	<20	66	<0.01	<10	5	<10	6	73
12	13369	2.9	0.21	70	<5	<5	0.12	<1	11	86	67	9.60	<10	0.15	<1	3	<0.01	5	100	30	<5	<20	6	<0.01	<10	<1	<10	4	86
13	13370	2.5	0.14	45	<5	<5	0.09	<1	9	78	57	8.60	<10	0.13	<1	3	<0.01	3	80	22	<5	<20	4	<0.01	<10	<1	<10	3	68
14	13371	2.3	0.16	25	<5	<5	0.03	<1	9	93	75	4.97	<10	0.08	<1	4	<0.01	9	<10	8	<5	<20	4	<0.01	<10	<1	<10	2	23
15	13372	1.0	0.55	20	10	<5	0.35	<1	13	101	246	4.32	<10	0.47	123	2	<0.01	8	150	10	10	<20	9	<0.01	<10	12	<10	3	332
16	13373	0.2	0.25	<5	160	<5	0.58	<1	<1	80	12	0.30	10	0.02	264	2	0.03	4	30	28	<5	<20	21	<0.01	<10	<1	<10	5	49
17	13374	0.6	0.24	65	<5	<5	0.65	<1	6	83	32	4.22	<10	0.13	53	3	<0.01	6	460	16	<5	<20	8	<0.01	<10	<1	<10	3	40
18	13375	<0.2	3.79	5	50	<5	1.87	<1	31	340	65	3.99	<10	3.66	804	11	0.17	167	1950	26	<5	<20	229	0.18	<10	83	<10	5	166
19	13376	0.7	0.51	70	<5	<5	0.66	<1	9	86	37	4.79	<10	0.39	96	4	<0.01	16	580	20	5	<20	7	0.02	<10	7	<10	5	55
20	13377	0.2	3.55	10	35	<5	2.85	<1	31	163	68	4.17	<10	2.36	601	7	0.28	75	1390	30	<5	<20	163	0.12	<10	81	<10	5	91
21	13378	0.5	0.28	30	<5	5	0.36	<1	10	60	30	5.51	<10	0.16	<1	4	0.01	4	630	18	<5	<20	4	<0.01	<10	1	<10	5	35
22	13379	0.4	0.53	30	<5	<5	0.50	<1	10	92	52	4.74	<10	0.36	71	2	0.03	23	770	22	<5	<20	8	0.04	<10	6	<10	5	120
23	13380	0.5	0.22	70	<5	<5	0.46	<1	9	72	42	6.66	<10	0.15	<1	<1	<0.01	8	770	46	<5	<20	4	<0.01	<10	1	<10	6	183
24	13381	0.7	0.24	115	<5	<5	0.36	<1	12	79	36	7.97	<10	0.15	<1	3	<0.01	2	710	48	<5	<20	5	<0.01	<10	<1	<10	7	87
25	13382	0.9	0.27	80	<5	<5	0.40	<1	11	74	38	7.07	<10	0.14	<1	3	<0.01	3	720	156	<5	<20	7	0.02	<10	<1	<10	7	286
26	13383	0.6	0.24	80	<5	<5	0.36	<1	8	89	29	6.52	<10	0.11	<1	<1	<0.01	3	680	56	<5	<20	5	0.01	<10	<1	<10	6	425
27	13384	0.4	0.27	20	<5	<5	0.34	<1	8	87	38	6.78	<10	0.12	<1	1	0.01	3	750	34	<5	<20	7	<0.01	<10	<1	<10	6	79

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC DATA:																													
Resplit:																													
1	13358	0.5	0.35	10	105	<5	2.26	<1	3	49	56	1.36	<10	0.52	475	<1	<0.01	8	150	42	20	<20	48	<0.01	<10	4	<10	5	114
Repeat:																													
1	13358	0.5	0.36	10	140	<5	2.20	<1	3	54	55	1.29	<10	0.50	466	<1	<0.01	9	130	44	25	<20	47	<0.01	<10	4	<10	5	98
10	13367	0.2	2.06	<5	195	<5	1.55	<1	18	95	52	3.15	<10	1.24	341	13	0.23	33	770	24	<5	<20	113	0.20	<10	43	<10	8	55
19	13376	0.6	0.51	75	<5	<5	0.67	<1	9	87	35	4.82	<10	0.39	99	4	<0.01	17	580	22	<5	<20	7	0.02	<10	6	<10	5	52
Standard:																													
GEO '03		1.6	1.57	55	140	<5	1.57	<1	20	57	89	3.41	<10	0.94	624	6	0.02	29	630	18	<5	<20	40	0.11	<10	52	<10	9	76

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
df/247
XLS/03

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-249

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

28-Jul-03

ATTENTION: Bob Carmichael

No. of samples received: 11
Sample type: Core
Project #: Tulsquah Chief
Shipment #: 10
Samples submitted by: Redfern

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	13385	<0.03	<0.001					
2	13386	0.21	0.006	7.1	0.21	0.21	0.13	1.33
3	13387	0.03	0.001					
4	13388	0.08	0.002					
5	13389	0.03	0.001					
6	13390	0.51	0.015					
7	13391a	-	-	148	4.32	0.63	0.48	0.97
7	13391b	2.07	0.060					
8	13392	0.16	0.005					
9	13393	0.03	0.001					
10	13394a	-	-	312	9.10	1.49	11.3	14.7
10	13394b	2.06	0.060					
11	13395	0.07	0.002					
QC DATA:								
Repeat:								
1	13385	<0.03	<0.001					
Resplit:								
1	13385	<0.03	<0.001					
Standard:								
PM168		2.08	0.061					
Mpla				70.0	2.04	1.43	4.35	19.0

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
XLS/03

25-Jul-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-249

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 11
Sample type: Core
Project #: Tulsquah Chief
Shipment #: 10
Samples submitted by: Redfern

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	13385	<0.2	2.89	<5	670	<5	1.06	<1	6	55	103	2.04	<10	2.15	384	<1	0.16	12	216	29	<5	<20	110	0.02	<10	7	<10	6	338
2	13386	6.4	0.81	125	15	<5	0.52	60	8	55	2086	4.32	<10	0.72	52	<1	0.05	<1	228	1188	10	<20	74	<0.01	<10	4	<10	5	>10000
3	13387	<0.2	1.66	<5	125	<5	0.56	<1	5	38	37	2.20	<10	2.13	253	<1	0.02	8	312	24	<5	<20	34	<0.01	<10	6	<10	5	592
4	13388	2.7	0.86	30	30	<5	0.59	18	6	41	772	3.10	<10	1.18	127	7	<0.01	6	192	216	<5	<20	115	<0.01	<10	2	<10	4	4125
5	13389	0.2	0.64	10	120	<5	0.35	<1	4	62	11	1.14	<10	0.75	97	8	<0.01	5	168	48	<5	<20	50	<0.01	<10	2	<10	2	169
6	13390	5.4	0.40	190	<5	<5	0.36	<1	10	31	215	5.41	<10	0.45	<1	1	<0.01	6	84	134	40	<20	20	<0.01	<10	2	<10	2	208
7	13391	>30	1.48	560	25	<5	0.19	43	7	26	6320	3.52	<10	1.78	214	<1	0.03	8	568	4318	180	<20	18	<0.01	<10	4	<10	2	9505
8	13392	1.4	0.25	35	20	<5	0.52	<1	10	55	53	3.80	<10	0.21	37	1	<0.01	4	72	43	5	<20	30	<0.01	<10	1	<10	2	264
9	13393	0.4	0.18	<5	65	<5	0.73	<1	4	128	18	1.10	<10	0.21	208	2	<0.01	8	36	7	<5	<20	12	<0.01	<10	1	<10	<1	24
10	13394	>30	0.13	1750	5	<5	0.14	789	5	22	9979	4.00	<10	0.14	48	<1	<0.01	<1	658	>10000	1086	<20	22	<0.01	<10	5	<10	<1	>10000
11	13395	0.4	4.93	10	360	<5	3.12	<1	30	114	210	5.56	12	3.78	1338	<1	0.17	54	948	46	<5	<20	80	0.12	<10	161	<10	8	544
QC DATA:																													
Resplit:																													
1	13385	<0.2	2.93	<5	672	<5	1.07	<1	6	54	97	2.08	<10	2.15	388	<1	0.16	14	228	31	<5	<20	108	0.02	<10	8	<10	6	347
Repeat:																													
1	13385	<0.2	2.76	<5	570	<5	1.04	<1	6	54	103	2.02	<10	2.16	378	<1	0.15	12	228	31	<5	<20	100	0.01	<10	8	<10	5	347
Standard:																													
GEO '03		1.5	1.70	60	150	<5	1.63	<1	20	62	90	3.71	12	1.00	628	<1	0.02	32	684	22	<5	<20	44	0.11	<10	74	<10	11	74

JJ/kk
df/251
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

AUG 4 2003

CERTIFICATE OF ASSAY AK 2003-251

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

25-Jul-03

ATTENTION: **Bob Carmichael**

No. of samples received: 51
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 8
Samples Submitted by: T.Z.

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	13307	0.03	0.001					
2	13308	0.04	0.001					
3	13309	0.04	0.001					
4	13310	0.04	0.001					
5	13311	0.07	0.002					
6	13312	<0.03	<0.001					
7	13313	0.06	0.002					
8	13314	0.06	0.002					
9	13315	0.09	0.003					
10	13316	0.10	0.003					
11	13317	0.08	0.002					
12	13318	0.08	0.002					
13	13319a			308	8.98	1.47	9.60	14.6
13	13319b	2.05	0.060					
14	13320	0.10	0.003					
15	13321	0.09	0.003					
16	13322	0.12	0.003					
17	13323	0.12	0.003					
18	13324	0.12	0.003					
19	13325	0.06	0.002					
20	13326	0.09	0.003					
21	13327	0.09	0.003					
22	13328	0.07	0.002					
23	13329	<0.03	<0.001					
24	13330	0.10	0.003					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. AK3-251

25-Jul-03

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
25	13331	0.12	0.003					
26	13332	0.21	0.006					
27	13333	0.10	0.003					
28	13334	0.07	0.002					
29	13335	0.20	0.006					
30	13336	0.24	0.007					
31	13337	0.16	0.005					
32	13338	0.15	0.004					
33	13339	0.28	0.008					
34	13340	0.37	0.011					
35	13341	0.26	0.008					
36	13342	<0.03	<0.001					
37	13343	0.27	0.008					
38	13344	0.24	0.007					
39	13345	0.20	0.006					
40	13346	0.16	0.005					
41	13347	<0.03	<0.001					
42	13348	0.03	0.001					
43	13349	0.06	0.002					
44	13350	0.03	0.001					
45	13351	0.07	0.002					
46	13352a			144	4.20	0.64	0.47	1.00
46	13352b	2.09	0.061					
47	13353	0.08	0.002					
48	13354	0.09	0.003					
49	13355	0.04	0.001					
50	13356	0.27	0.008	4.2	0.12	0.09	0.24	1.41
51	13357	0.16	0.005					
QC DATA:								
Resplit:								
1	13307	0.03	0.001					
36	13342	<0.03	<0.001					
Repeat:								
1	13307	0.03	0.001					
10	13316	0.10	0.003					
19	13325	0.06	0.002					
36	13342	<0.03	<0.001					
Standard:								
PG107		2.08	0.061					
PG107		2.04	0.059					
Mpla				68.0	1.98	1.44	4.36	19.0
CU106				136	3.97	1.44		

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

25-Jul-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-251

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 51
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 8
Samples Submitted by: T.Z.

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	13307	0.3	0.59	20	10	<5	0.29	<1	7	56	20	6.16	20	0.51	93	<1	<0.01	2	800	12	<5	<20	10	<0.01	<10	2	<10	5	57
2	13308	0.3	0.37	40	<5	<5	0.29	<1	8	63	31	7.51	20	0.19	12	<1	0.01	2	910	20	<5	<20	11	<0.01	<10	<1	<10	6	51
3	13309	0.3	0.29	40	<5	<5	0.24	<1	8	71	25	7.08	10	0.14	15	<1	<0.01	<1	810	12	<5	<20	8	<0.01	<10	1	<10	4	64
4	13310	<0.2	0.22	35	<5	<5	0.19	<1	10	81	29	8.70	20	0.14	16	<1	<0.01	<1	620	16	<5	<20	7	<0.01	<10	<1	<10	4	187
5	13311	0.5	0.25	65	15	<5	0.19	<1	7	66	191	5.58	10	0.10	21	<1	<0.01	<1	660	16	<5	<20	8	<0.01	<10	<1	<10	4	78
6	13312	<0.2	2.01	<5	115	<5	1.52	<1	18	82	32	3.35	10	1.14	316	2	0.25	29	800	22	<5	<20	120	0.21	<10	44	<10	9	46
7	13313	0.9	0.23	90	5	<5	0.16	<1	8	69	200	6.59	10	0.11	8	<1	<0.01	<1	580	32	<5	<20	6	<0.01	<10	<1	<10	3	165
8	13314	2.1	0.24	60	10	<5	0.16	<1	8	73	31	6.76	10	0.11	11	<1	<0.01	2	590	30	<5	<20	5	<0.01	<10	<1	<10	4	230
9	13315	1.0	0.30	75	<5	<5	0.19	<1	8	85	39	7.12	10	0.12	18	<1	<0.01	1	690	26	<5	<20	6	<0.01	<10	<1	<10	4	139
10	13316	0.7	0.24	100	<5	<5	0.26	<1	7	70	97	7.14	10	0.13	19	<1	<0.01	<1	660	38	<5	<20	5	<0.01	<10	<1	<10	4	163
11	13317	0.5	0.26	70	5	<5	0.25	<1	7	63	40	5.52	10	0.10	11	<1	<0.01	<1	670	38	<5	<20	5	<0.01	<10	<1	<10	4	144
12	13318	0.9	0.32	150	<5	<5	0.33	<1	6	76	199	4.65	10	0.10	11	<1	<0.01	1	710	34	10	<20	8	<0.01	<10	<1	<10	6	106
13	13319	>30	0.12	1965	<5	<5	0.11	869	5	22	>10000	4.25	<10	0.14	45	<1	<0.01	<1	650	>10000	1030	<20	22	<0.01	<10	5	<10	<1	>10000
14	13320	2.5	0.25	104	<5	<5	0.29	<1	10	62	51	6.57	13	0.13	21	<1	<0.01	2	697	160	<5	<20	4	<0.01	<10	<1	<10	7	123
15	13321	2.6	0.23	480	85	<5	0.19	3	<1	93	47	8.30	10	0.14	15	15	<0.01	42	<10	<2	115	<20	32	<0.01	<10	4	<10	<1	300
16	13322	1.3	0.22	75	<5	<5	0.16	<1	12	98	89	>10	20	0.16	15	<1	<0.01	1	410	30	<5	<20	3	<0.01	<10	1	<10	4	376
17	13323	1.5	0.21	330	<5	<5	0.21	<1	13	89	4169	>10	20	0.16	14	<1	<0.01	1	810	16	25	<20	4	<0.01	<10	<1	<10	4	292
18	13324	1.0	0.21	205	<5	<5	0.21	<1	13	82	4641	>10	20	0.16	13	<1	<0.01	2	830	12	10	<20	3	<0.01	<10	<1	<10	4	260
19	13325	0.3	0.27	60	<5	<5	0.22	<1	8	92	70	6.78	10	0.12	12	<1	<0.01	3	670	12	<5	<20	4	<0.01	<10	<1	<10	5	86
20	13326	1.8	0.23	215	<5	<5	0.22	<1	8	87	442	8.09	10	0.13	8	<1	<0.01	1	510	28	10	<20	4	<0.01	<10	<1	<10	4	365
21	13327	2.3	0.25	715	<5	<5	0.24	<1	10	96	3723	>10	20	0.17	9	<1	<0.01	2	550	32	25	<20	4	<0.01	<10	<1	<10	4	340
22	13328	0.4	0.35	60	<5	<5	0.36	<1	8	76	223	6.98	10	0.18	7	<1	0.02	1	490	30	<5	<20	7	<0.01	<10	2	<10	4	205
23	13329	<0.2	2.53	15	100	<5	1.68	<1	11	63	77	2.78	<10	0.88	687	<1	0.29	9	1450	40	<5	<20	30	0.10	<10	30	<10	3	217
24	13330	0.7	0.44	85	5	<5	0.42	<1	9	75	121	4.31	<10	0.16	36	<1	0.01	6	360	38	5	<20	2	0.01	<10	4	<10	4	135
25	13331	1.2	0.20	150	<5	<5	0.18	<1	27	78	57	8.78	10	0.16	6	<1	<0.01	18	190	48	<5	<20	3	0.03	<10	<1	<10	5	194

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	13332	1.1	0.34	375	<5	<5	0.36	<1	43	81	72	>10	20	0.21	6	<1	<0.01	25	540	54	<5	<20	5	0.04	<10	5	<10	8	211
27	13333	1.0	0.25	155	<5	<5	0.25	<1	59	73	79	6.35	<10	0.14	8	<1	<0.01	39	170	36	<5	<20	4	0.02	<10	4	<10	6	159
28	13334	1.3	0.26	115	<5	<5	0.20	<1	45	74	116	7.91	10	0.14	9	<1	<0.01	23	280	56	<5	<20	3	0.02	<10	7	<10	5	251
29	13335	2.9	0.24	175	<5	<5	0.20	<1	31	90	154	9.25	10	0.16	15	<1	<0.01	15	250	52	<5	<20	4	0.01	<10	6	<10	4	420
30	13336	5.7	0.23	155	<5	<5	0.12	<1	32	90	77	>10	10	0.17	12	<1	<0.01	15	<10	40	<5	<20	4	<0.01	<10	7	<10	3	157
31	13337	4.8	0.23	205	<5	<5	0.17	<1	22	116	94	>10	10	0.18	11	<1	<0.01	10	50	52	<5	<20	2	<0.01	<10	8	<10	4	151
32	13338	4.8	0.20	225	<5	<5	0.17	<1	23	88	102	>10	10	0.18	12	<1	<0.01	10	40	54	<5	<20	2	<0.01	<10	7	<10	3	154
33	13339	7.1	0.25	290	<5	<5	0.19	<1	22	102	348	>10	<10	0.22	11	<1	<0.01	11	250	108	10	<20	3	0.01	<10	8	<10	4	292
34	13340	5.9	0.26	430	<5	<5	0.20	<1	23	84	391	>10	<10	0.20	20	<1	<0.01	9	420	88	30	<20	3	<0.01	<10	10	<10	4	181
35	13341	3.6	0.29	115	<5	<5	0.15	<1	22	77	83	8.50	10	0.19	11	<1	<0.01	7	220	76	<5	<20	3	0.02	<10	7	<10	5	96
36	13342	<0.2	1.96	<5	135	<5	1.84	<1	25	93	36	3.61	<10	1.26	373	3	0.19	34	890	34	<5	<20	94	0.22	<10	36	<10	10	59
37	13343	4.9	0.23	155	55	<5	0.20	<1	24	92	89	>10	<10	0.29	12	<1	<0.01	3	270	124	<5	<20	2	0.01	<10	4	<10	5	66
38	13344	15.0	0.36	115	50	<5	0.36	<1	41	60	87	>10	<10	0.35	14	<1	<0.01	12	450	124	10	<20	6	0.02	<10	8	<10	7	34
39	13345	5.8	0.70	195	45	<5	0.44	<1	46	62	109	>10	<10	0.49	12	<1	0.02	17	650	48	5	<20	9	0.10	<10	3	<10	11	32
40	13346	3.9	1.33	410	45	<5	0.79	<1	57	51	130	>10	10	1.08	241	<1	0.02	37	1840	42	<5	<20	11	0.10	<10	12	<10	13	59
41	13347	0.6	3.17	55	50	<5	0.70	<1	44	61	235	9.29	10	3.04	1035	<1	0.03	21	770	44	<5	<20	10	0.23	<10	45	<10	13	211
42	13348	0.7	2.43	40	40	<5	0.65	<1	44	52	428	7.22	10	2.01	736	<1	0.03	17	780	32	<5	<20	14	0.19	<10	36	<10	13	123
43	13349	1.3	2.11	105	45	<5	0.61	<1	44	50	166	7.77	<10	1.79	736	<1	0.02	19	770	30	<5	<20	13	0.20	<10	21	<10	14	125
44	13350	0.2	3.34	45	45	<5	0.74	<1	40	75	465	8.44	<10	3.01	1178	<1	0.04	27	770	36	<5	<20	64	0.22	<10	58	<10	13	214
45	13351	0.5	4.97	90	60	<5	2.82	<1	47	372	139	7.09	<10	4.66	1317	<1	0.25	190	2440	50	<5	<20	173	0.23	<10	95	<10	8	125
46	13352	>30	1.64	625	<5	<5	0.22	44	8	30	6147	3.79	<10	1.69	232	<1	0.03	6	560	4526	180	<20	15	<0.01	<10	3	<10	2	9876
47	13353	0.6	1.63	11	12	<5	1.31	2	5	77	94	3.28	10	0.60	296	2	0.14	8	193	157	3	<20	45	0.01	<10	<1	<10	5	587
48	13354	1.6	2.17	200	45	<5	2.69	51	16	124	872	4.94	<10	0.98	405	25	0.14	98	480	128	115	<20	40	0.04	<10	11	<10	7	8456
49	13355	0.8	2.18	15	<5	<5	2.36	39	9	98	191	2.59	<10	1.00	713	29	0.15	26	540	280	160	<20	1	0.02	60	22	<10	17	7498
50	13356	4.0	1.25	<5	<5	<5	1.25	89	7	103	865	2.66	<10	0.64	381	28	0.07	10	280	3302	125	<20	4	0.03	<10	21	<10	13	>10000
51	13357	0.7	1.39	<5	<5	<5	1.76	6	8	80	59	1.84	10	0.52	369	21	0.11	21	630	304	120	<20	<1	0.02	20	37	<10	31	1056

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-269

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

1-Aug-03

ATTENTION: Bob Carmichael

No. of samples received: 41
Sample type: Core
Project #: Tulequah Chief
Shipment #: 11
Samples Submitted by: Redfern Resources

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	13396	0.09	0.003					
2	13397	0.04	0.001					
3	13398	0.55	0.016					
4	13399	0.43	0.013	46.7	1.36	0.04	0.42	0.59
5	13400	0.15	0.004					
6	13401	0.12	0.003					
7	13402	0.22	0.006					
8	13403	0.16	0.005					
9	13404	0.12	0.003					
10	13405	0.10	0.003					
11	13406	0.12	0.003					
12	13407	0.16	0.005					
13	13408	0.14	0.004					
14	13409	0.15	0.004					
15	13410	0.10	0.003					
16	13411	0.13	0.004					
17	13412	0.04	0.001					
18	13413	0.04	0.001					
19	13414	0.27	0.008					
20	13415	0.13	0.004					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
21	13416	0.11	0.003					
22	13417	0.09	0.003					
23	13418a			318	9.27	1.50	9.63	14.9
23	13418b	2.11	0.062					
24	13419	0.05	0.001					
25	13420	0.03	0.001					
26	13421	0.05	0.001					
27	13422	0.03	0.001					
28	13423	<0.03	<0.001					
29	13424	<0.03	<0.001					
30	13425	0.04	0.001					
31	13426	0.00	0.000					
32	13427	0.03	0.001					
33	13428	0.04	0.001					
34	13429	<0.03	<0.001					
35	13430	0.07	0.002					
36	13431	0.09	0.003					
37	13432	0.05	0.001					
38	13433	0.04	0.001					
39	13434	<0.03	<0.001					
40	13435	<0.03	<0.001					
41	13436	<0.03	<0.001					
QC DATA:								
Repeat:								
1	13396	0.10	0.003					
10	13405	0.11	0.003					
19	13414	0.08	0.002					
36	13431	0.09	0.003					
Resplit:								
1	13396	0.09	0.003					
36	13431	0.09	0.003					
Standard:								
PM164		3.26	0.095					
PM906		5.60	0.163					

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %
26	13421	0.2	1.04	10	60	<5	0.45	5	5	55	41	2.11	<10	1.12	1577	<1	<0.01	8	210	166	<5	<20	6	<0.01
27	13422	0.5	3.86	10	60	<5	3.77	<1	21	81	40	3.66	<10	1.61	3970	<1	0.15	50	340	138	<5	<20	32	0.06
28	13423	0.3	7.87	20	110	<5	4.86	<1	48	340	101	5.70	<10	3.86	5978	<1	0.29	150	590	52	<5	<20	49	0.20
29	13424	0.3	7.62	20	205	<5	5.64	<1	57	426	102	6.35	10	3.89	7063	15	0.20	181	640	76	<5	<20	20	1.01
30	13425	0.8	1.61	25	75	<5	2.33	13	17	86	94	4.50	<10	0.87	2660	3	0.04	23	470	170	<5	<20	<1	0.32
31	13426	2.1	1.40	55	35	<5	1.77	7	24	81	473	8.39	<10	0.96	2823	2	<0.01	19	870	302	<5	<20	<1	0.31
32	13427	<0.2	0.99	25	40	<5	0.97	22	10	65	305	4.25	<10	0.58	1333	<1	0.01	7	660	40	<5	<20	3	0.03
33	13428	1.0	0.69	20	65	<5	1.89	<1	13	70	54	2.90	<10	0.61	1142	3	<0.01	16	240	58	10	<20	32	0.11
34	13429	0.3	1.74	5	155	<5	4.61	<1	18	78	61	4.77	20	1.69	1099	<1	0.03	26	2160	10	<5	<20	213	<0.01
35	13430	0.8	0.55	45	15	<5	2.06	<1	22	47	1474	4.36	<10	0.45	923	1	<0.01	19	750	49	5	<20	68	0.01
36	13431	0.7	0.80	20	45	<5	1.54	<1	11	53	68	2.51	<10	0.70	975	<1	0.01	9	230	38	10	<20	68	0.01
37	13432	0.6	1.50	20	70	<5	0.91	4	11	72	103	4.56	<10	1.64	1585	<1	<0.01	12	610	18	<5	<20	16	0.02
38	13433	2.2	4.47	<5	65	<5	1.71	<1	51	129	182	6.80	<10	4.09	2891	<1	0.03	61	560	26	<5	<20	14	0.16
39	13434	<0.2	1.88	<5	50	<5	0.42	<1	10	60	12	3.85	<10	1.87	1767	<1	<0.01	12	530	10	<5	<20	10	0.02
40	13435	0.2	2.09	175	25	<5	0.57	<1	9	71	19	6.35	<10	1.97	2439	<1	<0.01	12	1150	18	<5	<20	19	0.02
41	13436	0.2	1.63	140	25	<5	0.40	<1	8	63	8	5.73	<10	1.31	1395	<1	<0.01	6	870	22	<5	<20	11	0.03
QC DATA:																								
Resplit:																								
1	13396	1.8	1.76	45	20	<5	1.31	7	20	150	320	4.49	<10	1.50	255	4	0.12	74	850	116	<5	<20	53	0.04
36	13431	0.6	0.77	20	45	<5	1.54	<1	11	56	61	2.52	<10	0.68	991	2	0.01	11	220	40	10	<20	68	0.01
Repeat:																								
1	13396	1.8	1.73	50	20	<5	1.12	8	19	131	320	4.03	<10	1.47	221	3	0.12	64	760	98	<5	<20	59	0.03
10	13405	1.7	0.85	45	45	<5	0.68	4	6	64	79	3.57	<10	0.56	305	1	0.06	3	1380	42	10	<20	16	<0.01
19	13414	1.5	0.31	60	20	<5	0.28	2	16	63	129	4.51	<10	0.25	351	<1	<0.01	9	210	136	20	<20	4	<0.01
Standard:																								
GEO '03		1.6	1.52	60	145	<5	1.63	<1	19	60	89	3.74	10	1.00	689	<1	0.02	30	680	20	<5	<20	47	0.11
GEO '03		1.6	1.54	60	155	<5	1.62	<1	21	61	83	4.02	<10	0.95	716	<1	0.01	31	670	22	<5	<20	45	0.10

JJ/kk
dl/269
XLS/03

ECO TECH LABORATORY L
Jutta Jealouse
B.C. Certified Assayer

1-Aug-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-269

REDFE
760-777
Vancou
V6Z 1S

ATTEN

No. of s
Sample
Project
Shipme
Sample

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %
1	13396	1.8	1.86	50	25	<5	1.15	8	19	136	348	4.13	<10	1.57	231	3	0.14	67	810	100	<5	<20	62	0.04
2	13397	0.5	2.83	10	65	<5	1.99	<1	17	152	32	2.83	<10	2.32	630	<1	0.19	70	870	38	<5	<20	143	0.03
3	13398	12.7	0.41	70	15	<5	0.25	7	4	46	216	2.35	10	0.22	58	<1	0.03	<1	10	356	10	<20	25	<0.01
4	13399	>30	1.09	110	50	<5	0.41	35	8	35	438	3.05	<10	0.78	330	<1	0.06	11	120	4125	20	<20	29	0.03
5	13400	5.9	0.82	60	30	<5	0.34	3	14	62	213	4.70	10	0.61	271	<1	0.04	7	170	164	10	<20	15	0.04
6	13401	3.7	0.25	75	10	<5	0.21	<1	8	81	36	8.89	20	0.23	<1	7	0.02	7	340	52	<5	<20	4	0.06
7	13402	4.0	0.37	100	<5	<5	0.50	<1	8	76	98	>10	10	0.31	<1	<1	0.03	1	1880	46	<5	<20	7	<0.01
8	13403	4.6	0.29	135	<5	<5	0.48	<1	17	85	62	>10	10	0.33	<1	<1	0.02	2	1610	88	<5	<20	3	<0.01
9	13404	3.2	0.44	70	<5	<5	0.35	<1	7	68	32	7.63	<10	0.35	65	<1	0.03	1	640	54	<5	<20	6	<0.01
10	13405	1.6	0.88	45	40	<5	0.64	4	5	62	79	3.40	<10	0.58	299	1	0.06	3	1330	38	5	<20	16	<0.01
11	13406	2.4	0.60	45	15	<5	0.39	<1	14	64	67	5.02	<10	0.46	206	<1	0.04	3	550	202	10	<20	9	<0.01
12	13407	2.5	0.53	85	<5	<5	0.26	<1	16	59	63	6.63	<10	0.52	211	1	0.02	2	620	224	10	<20	3	<0.01
13	13408	4.0	0.93	75	<5	<5	0.58	<1	13	78	144	>10	10	1.11	458	<1	0.03	5	1940	398	<5	<20	6	<0.01
14	13409	3.5	0.78	35	<5	<5	0.30	<1	18	45	92	6.31	<10	0.86	668	3	0.02	10	250	298	10	<20	4	<0.01
15	13410	0.9	1.31	30	20	<5	0.29	<1	9	43	43	5.89	<10	1.39	1016	<1	0.02	6	700	110	<5	<20	7	<0.01
16	13411	1.8	1.55	75	<5	<5	0.52	3	11	73	143	>10	<10	1.68	1508	<1	0.02	4	1160	336	<5	<20	9	<0.01
17	13412	<0.2	1.92	<5	145	<5	1.49	<1	19	86	34	3.53	<10	1.16	345	2	0.20	28	820	22	<5	<20	91	0.16
18	13413	0.4	0.35	30	30	<5	0.30	<1	7	47	31	2.67	<10	0.25	287	<1	0.01	<1	370	114	5	<20	3	<0.01
19	13414	1.4	0.30	70	30	<5	0.27	3	15	66	120	4.38	<10	0.24	354	2	<0.01	10	220	132	20	<20	4	0.01
20	13415	1.8	0.35	50	10	<5	0.27	16	12	63	250	5.75	<10	0.32	384	<1	<0.01	3	160	164	25	<20	3	<0.01
21	13416	1.0	0.32	90	10	<5	0.28	11	7	87	159	7.08	<10	0.30	257	<1	<0.01	4	380	134	<5	<20	2	0.05
22	13417	1.7	0.32	45	15	<5	0.61	6	6	51	103	3.42	<10	0.28	237	<1	<0.01	7	260	178	10	<20	6	<0.01
23	13418	>30	0.11	1955	<5	<5	0.14	901	6	23	>10000	4.10	<10	0.14	43	<1	<0.01	<1	720	>10000	990	<20	21	<0.01
24	13419	0.6	0.53	10	<5	<5	0.36	7	<1	63	13	2.20	<10	0.55	474	5	<0.01	11	<10	32	40	<20	<1	<0.01
25	13420	0.4	0.58	10	60	<5	0.41	<1	4	47	18	1.52	<10	0.63	780	2	<0.01	8	170	144	<5	<20	5	<0.01

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-285

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

14-Aug-03

ATTENTION: Bob Carmichael

No. of samples received: 41
Sample type: Core
Project #:Tulequah Chief
Shipment #: 12
Samples submitted by: Redfern

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	13437	0.19	0.006					
2	13438	0.54	0.016					
3	13439	3.23	0.094	256	7.47	0.27	2.06	12.80
4	13440	0.65	0.019					
5	13441	0.82	0.024					
6	13442	0.04	<0.001					
7	13443	0.20	0.006					
8	13444	0.85	0.025					
9	13445	0.75	0.022					
10	13446	0.30	0.009					
11	13447	0.11	0.003					
12	13448	0.05	0.001					
13	13449	0.15	0.004					
14	13450	0.13	0.004					
15	13451	0.14	0.004					
16A	13452	2.03	0.059					
16B	13452	0.14	0.004	142	4.14	0.62	0.46	1.01
17	13453	0.16	0.005					
18	13454	0.18	0.005					
19	13455	0.27	0.008					
20	13456	0.07	0.002					
21	13457	0.26	0.008					
22	13458	0.18	0.005					
23	13459	0.04	0.001					
24	13460	0.03	0.001					
25	13461	0.29	0.008					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. AK3-285 14-Aug-03

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	13462	0.02	0.001
27	13463	0.05	0.001
28	13464	<0.03	<0.001
29	13465	<0.03	<0.001
30	13466	0.06	0.002
31	13467	<0.03	<0.001
32	13468	0.07	0.002
33	13469	<0.03	<0.001
34	13470	<0.03	<0.001
35	13471	0.05	0.001
36	13472	0.04	0.001
37	13473	0.08	0.002
38	13474	0.03	0.001
39	13475	0.03	0.001
40	13476	0.03	0.001
41	13477	<0.03	<0.001
QC DATA:			
Repeat:			
1	13437	0.11	0.003
10	13446	0.32	0.009
19	13455	0.21	0.006
36	13472	0.03	0.001
Resplit:			
1	13437	0.30	0.009
36	13472	0.03	0.001
Standard:			
PM164		3.12	0.091
PM164		3.23	0.094

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

8-Aug-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-285

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 41
Sample type: Core
Project #:Tulequah Chief
Shipment #: 12
Samples submitted by: Redfern

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	13437	3.2	3.32	<5	440	<5	1.35	2	6	65	395	2.17	<10	1.48	250	1	0.24	10	220	78	<5	<20	182	0.04	<10	<1	<10	4	710
2	13438	3.8	3.30	<5	465	<5	1.31	2	6	76	555	2.19	<10	1.50	250	1	0.24	9	250	114	<5	<20	175	0.04	<10	<1	<10	5	641
3	13439	>30	0.95	1080	55	<5	1.51	454	8	40	2474	2.93	<10	0.25	87	<1	0.08	<1	140	>10000	180	<20	90	<0.01	<10	4	<10	2	>10000
4	13440	17.4	1.12	70	70	<5	0.57	1	9	32	98	2.73	<10	0.43	77	2	0.09	5	100	562	10	<20	69	0.01	<10	5	<10	3	1063
5	13441	8.3	1.03	335	25	<5	0.13	<1	11	61	60	5.27	<10	0.94	174	<1	0.06	8	140	104	5	<20	7	0.02	<10	4	<10	4	553
6	13442	0.2	2.20	<5	150	<5	1.80	<1	21	96	25	3.40	10	1.38	382	4	0.25	28	870	26	<5	<20	116	0.18	<10	33	<10	8	54
7	13443	0.7	1.10	50	60	<5	0.12	<1	6	47	21	2.10	<10	0.99	191	1	0.06	4	170	18	<5	<20	5	0.01	<10	3	<10	2	130
8	13444	0.8	1.04	230	35	<5	0.18	<1	8	56	55	2.84	<10	0.81	160	2	0.07	4	70	28	<5	<20	8	0.01	<10	5	<10	2	121
9	13445	0.4	0.66	75	90	<5	0.10	<1	5	41	61	1.66	<10	0.34	67	5	0.06	2	80	12	5	<20	5	<0.01	<10	4	<10	1	51
10	13446	0.6	0.74	65	55	<5	0.14	<1	8	42	31	2.94	<10	0.45	85	<1	0.06	4	90	16	<5	<20	6	<0.01	<10	3	<10	2	62
11	13447	2.2	0.63	155	60	<5	0.19	<1	9	36	21	4.24	<10	0.22	47	2	0.07	1	50	46	<5	<20	6	<0.01	<10	4	<10	2	107
12	13448	0.6	0.50	65	130	<5	0.08	<1	4	21	11	1.00	<10	0.17	45	1	0.05	<1	70	12	<5	<20	6	0.02	<10	3	<10	1	28
13	13449	1.5	0.71	80	70	<5	0.33	<1	6	37	29	2.65	<10	0.28	55	<1	0.07	3	80	20	<5	<20	18	0.02	<10	3	<10	2	49
14	13450	1.1	0.76	55	80	<5	0.11	<1	6	48	16	2.66	<10	0.38	60	2	0.07	3	70	14	<5	<20	8	<0.01	<10	2	<10	2	28
15	13451	1.0	0.59	55	75	<5	0.16	<1	5	73	13	1.88	<10	0.37	90	3	0.05	4	60	14	<5	<20	19	<0.01	<10	2	<10	2	45
16B	13452	>30	1.70	640	90	<5	0.21	44	8	28	6049	3.95	<10	1.76	219	<1	0.05	6	660	4424	290	<20	19	0.04	<10	4	<10	3	9576
17	13453	0.6	0.76	40	110	<5	0.89	<1	4	98	9	1.80	<10	0.61	214	9	0.05	8	60	24	<5	<20	61	<0.01	<10	4	<10	1	87
18	13454	0.7	0.88	30	70	<5	0.11	<1	10	52	13	2.54	<10	0.73	178	<1	0.05	8	150	14	<5	<20	8	<0.01	<10	3	<10	2	86
19	13455	0.9	1.02	40	70	<5	0.11	<1	11	65	14	3.19	<10	0.88	192	2	0.06	6	160	18	<5	<20	8	<0.01	<10	4	<10	2	91
20	13456	0.8	1.07	25	35	<5	0.12	<1	7	62	13	3.28	<10	1.04	186	1	0.05	4	190	18	<5	<20	8	0.02	<10	4	<10	3	82
21	13457	1.3	1.03	30	75	<5	0.19	<1	7	55	25	2.81	<10	0.82	162	<1	0.07	6	180	42	<5	<20	12	0.02	<10	4	<10	2	116
22	13458	4.7	0.95	105	70	<5	0.11	4	8	48	151	2.69	<10	0.81	127	2	0.05	2	170	450	15	<20	7	<0.01	<10	4	<10	2	1192
23	13459	3.4	1.02	45	80	<5	0.09	<1	10	52	40	3.78	<10	0.95	170	2	0.04	4	90	36	<5	<20	6	<0.01	<10	6	<10	3	115
24	13460	2.1	1.58	25	130	<5	0.38	<1	10	62	25	3.37	<10	1.61	376	<1	0.06	18	320	186	<5	<20	9	<0.01	<10	17	<10	4	352
25	13461	4.7	0.42	315	25	<5	0.06	4	17	79	445	>10	10	0.20	<1	<1	0.03	<1	50	158	30	<20	3	<0.01	<10	2	<10	4	1948

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	13462	0.7	0.34	135	45	<5	0.15	1	6	107	164	3.68	<10	0.08	<1	5	0.03	2	280	70	15	<20	3	0.02	<10	2	<10	3	605
27	13463	1.7	0.34	1185	25	<5	0.12	<1	9	81	2850	7.11	<10	0.12	<1	1	0.03	3	460	76	180	<20	<1	0.02	<10	2	<10	4	1134
28	13464	0.4	0.30	150	5	<5	0.09	<1	16	66	908	6.20	<10	0.10	<1	2	0.03	6	160	34	15	<20	3	0.02	<10	2	<10	4	47
29	13465	0.6	0.56	40	5	<5	0.25	<1	15	41	2446	6.72	<10	0.12	<1	3	0.06	6	370	14	<5	<20	7	<0.01	<10	3	<10	4	55
30	13466	2.5	0.56	85	<5	<5	0.31	<1	49	61	5180	8.46	10	0.20	<1	<1	0.06	21	880	64	<5	<20	<1	<0.01	<10	16	<10	6	116
31	13467	0.3	2.01	<5	115	<5	1.56	<1	23	101	52	3.29	10	1.17	309	5	0.24	29	890	28	<5	<20	105	0.17	<10	29	<10	8	45
32	13468	2.7	0.71	110	<5	<5	0.44	<1	82	56	4340	>10	10	0.23	<1	<1	0.08	42	790	142	<5	<20	4	<0.01	<10	17	<10	7	170
33	13469	0.6	0.84	70	15	<5	0.56	<1	45	41	700	4.72	<10	0.20	19	<1	0.10	14	1090	62	<5	<20	4	<0.01	<10	20	<10	7	103
34	13470	0.9	0.75	75	15	<5	0.55	<1	44	31	1208	4.92	<10	0.23	33	<1	0.08	15	1100	42	<5	<20	6	0.02	<10	18	<10	7	184
35	13471	1.5	0.89	140	<5	<5	0.55	<1	76	57	1108	>10	10	0.27	<1	<1	0.10	32	590	144	<5	<20	8	0.02	<10	17	<10	7	91
36	13472	0.9	1.26	125	5	<5	0.60	<1	49	43	357	6.23	<10	0.55	153	<1	0.11	19	850	106	<5	<20	8	0.01	<10	31	<10	6	129
37	13473	2.7	1.10	120	<5	<5	0.61	1	72	68	1664	7.08	<10	0.45	107	<1	0.10	33	960	328	<5	<20	7	<0.01	<10	27	<10	7	488
38	13474	1.2	0.98	120	10	<5	0.51	<1	61	74	529	5.74	<10	0.39	100	<1	0.09	27	780	118	<5	<20	9	<0.01	<10	29	<10	5	88
39	13475	1.3	1.33	95	5	<5	0.58	<1	38	76	855	6.48	<10	0.66	192	2	0.10	18	830	124	<5	<20	10	0.02	<10	38	<10	6	264
40	13476	0.9	1.61	120	<5	<5	0.60	<1	38	77	168	9.99	10	1.00	317	<1	0.11	18	690	286	<5	<20	10	0.03	<10	47	<10	7	225
41	13477	0.4	1.93	130	15	<5	0.61	<1	33	59	56	6.02	<10	1.11	432	2	0.12	14	880	120	<5	<20	13	0.03	<10	55	<10	6	204
QC DATA:																													
Resplit:																													
1	13437	3.2	3.42	5	410	<5	1.43	3	6	74	420	2.26	<10	1.50	273	<1	0.25	10	280	82	5	<20	187	0.04	<10	<1	<10	5	773
36	13472	0.8	1.34	125	<5	<5	0.59	<1	49	45	331	6.41	<10	0.56	148	<1	0.12	19	840	110	<5	<20	5	0.01	<10	33	<10	7	119
Repeat:																													
1	13437	3.2	3.42	<5	500	<5	1.38	3	6	67	397	2.19	<10	1.49	255	1	0.25	10	240	78	<5	<20	188	0.04	<10	<1	<10	5	713
10	13446	0.6	0.74	65	55	<5	0.14	<1	8	42	32	2.96	<10	0.45	90	<1	0.06	3	90	16	<5	<20	6	<0.01	<10	3	<10	2	66
17	13453	0.6	0.80	40	120	<5	0.89	<1	4	98	9	1.81	<10	0.63	194	8	0.05	8	80	24	<5	<20	60	<0.01	<10	4	<10	2	90
Standard:																													
GEO '03		1.6	1.75	60	145	<5	1.78	<1	22	60	87	3.72	10	1.04	655	<1	0.03	32	800	22	<5	<20	45	0.12	<10	75	<10	11	78
GEO '03		1.6	1.77	50	140	<5	1.74	<1	21	61	86	3.74	10	1.01	635	1	0.03	32	780	24	5	<20	43	0.10	<10	73	<10	10	77

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
df/278
XLS/03

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-292

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

15-Aug-03

ATTENTION: Bob Carmichael

No. of samples received: 29
Sample type: Core
Project #:Tulequah Chief
Shipment #:13
Samples submitted by: Redfern

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	13479	36.7	1.070	1620	47.2	0.22	2.36	3.63
2	13480	7.23	0.211	228	6.65	0.03	0.27	0.66
3	13481	16.1	0.470	106	3.09	0.03	0.14	0.38
4	13482	0.60	0.017					
5	13483	4.05	0.118					
6	13484	0.09	0.003					
7	13485	0.10	0.003					
8	13486	0.14	0.004					
9	13487	0.51	0.015	18.0	0.53	0.15	0.19	1.23
10	13488	0.99	0.029	24.6	0.72	0.30	0.32	2.05
11	13489	0.36	0.010	15.2	0.44	0.16	0.11	0.57
12	13490	0.23	0.007	4.1	0.12	0.25	0.02	1.04
13	13491	2.03	0.059					
13	13491			146	4.26	0.62	0.45	1.01
14	13492	0.21	0.006					
15	13493	0.34	0.010	4.2	0.12	0.80	<0.01	2.03
16	13494	2.15	0.063					
16	13494			312	9.10	1.39	10.1	15.2
17	13495	0.25	0.007	5.1	0.15	0.63	0.01	1.11
18	13496	0.34	0.010	66.5	1.94	0.39	1.76	4.47
19	13497	0.15	0.004	48.1	1.40	0.15	0.25	0.82
20	13499	0.34	0.010					
21	13500	0.37	0.011					

ECO-TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. AK3-292

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
22	13501	0.41	0.012	24.4	0.71	0.34	1.08	3.22
23	13502	0.55	0.016	22.8	0.67	0.50	0.10	2.23
24	13503	0.27	0.008	18.7	0.55	0.80	0.22	2.51
25	13504	0.21	0.006	12.1	0.35	0.33	0.23	1.01
26	13505	0.38	0.011	40.2	1.17	0.18	0.66	3.89
27	13506	0.08	0.002	23.1	0.67	0.06	0.40	0.74
28	13507	0.03	0.001					
29	13508	0.16	0.005					
QC DATA:								
Repeat:								
1	13479	34.1	0.994					
1	13479	34.7	1.012					
2	13480	7.92	0.231					
3	13481	15.5	0.452					
5	13483	5.17	0.151					
19	13497	0.16	0.005					
Resplit:								
1	13479	30.9	0.901					
1	13479	35.5	1.035					
Standard:								
PM164		3.00	0.087					

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

15-Aug-03

ATTENTION: Bob Carmichael

Job #	ET #.	Tag #	SG g/cm^3
228	38	13228	2.81
238	19	13274	2.93
	20	13275	2.87
	22	13277	3.68
	23	13278	3.41
	24	13279	3.34
239	3	13284	4.25
	4	13285	3.78
	6	13287	3.60
	7	13288	3.44
	8	13289	2.82
	9	13290	2.83
	11	13292	3.91
	12	13293	4.13
	20	13301	3.34
	22	13303	3.45
	23	13304	3.17
247	6	13363	2.87
	7	13364	2.91
249	1	13385	2.77
251	50	13356	2.69
285	3	13439	3.13

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
XLS/03

REDFERN RESOURCES LTD.

15-Aug-03

Job #	ET #.	Tag #	SG g/cm^3
292	1	13479	2.86
	2	13480	2.70
	3	13481	2.68
	4	13482	2.76
	9	13487	2.71
	10	13488	2.75
	11	13489	2.83
	12	13490	2.66
	14	13492	2.64
	15	13493	2.83
	17	13495	2.77
	18	13496	3.00
	19	13497	2.80
	22	13501	2.92
	23	13502	2.73
	24	13503	2.89
	25	13504	2.81
	26	13505	2.70
	27	13506	2.67

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

15-Aug-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-292

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 29
Sample type: Core
Project #:Tulequah Chief
Shipment #:13
Samples submitted by: Redfern

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	13479	>30	0.41	680	50	<5	0.25	139	10	17	2294	0.73	<10	0.13	34	<1	0.02	<1	170	>10000	1635	<20	11	<0.01	<10	<1	<10	4	>10000
2	13480	>30	0.31	75	85	<5	0.22	18	4	52	282	0.31	<10	0.07	20	3	0.02	<1	30	2615	230	<20	65	<0.01	<10	1	<10	2	6553
3	13481	>30	0.37	95	80	<5	0.51	7	8	29	281	0.44	<10	0.16	43	3	0.02	3	40	1448	195	<20	52	<0.01	<10	2	<10	3	3636
4	13482	7.6	0.74	<5	<5	<5	0.72	9	10	42	159	3.11	<10	0.18	18	<1	0.05	<1	170	52	50	<20	2	0.01	<10	67	<10	41	216
5	13483	2.5	0.35	135	35	<5	0.43	<1	10	21	229	1.60	<10	0.14	23	3	0.03	4	120	50	95	<20	59	<0.01	<10	2	<10	3	355
6	13484	1.7	1.07	280	30	<5	0.85	<1	17	68	30	4.14	<10	1.03	165	1	0.08	28	580	28	20	<20	23	<0.01	<10	11	<10	6	126
7	13485	1.4	0.69	165	40	<5	0.50	4	12	38	26	2.38	<10	0.46	77	1	0.06	9	340	28	15	<20	9	<0.01	<10	3	<10	6	438
8	13486	5.3	1.33	15	95	<5	0.54	12	6	32	344	1.63	<10	0.89	276	8	0.09	5	380	392	5	<20	56	<0.01	<10	<1	<10	5	2349
9	13487	18.0	1.16	15	50	<5	0.56	60	6	55	1537	2.63	<10	0.80	204	10	0.06	<1	370	2076	5	<20	30	<0.01	<10	<1	<10	3	>10000
10	13488	26.9	1.08	20	40	<5	0.58	103	6	46	1867	3.46	<10	0.63	150	<1	0.07	<1	370	3236	15	<20	25	<0.01	<10	1	<10	3	>10000
11	13489	14.9	1.65	20	60	<5	1.44	34	7	91	1371	2.47	<10	0.64	232	7	0.11	6	530	1170	20	<20	40	<0.01	<10	4	<10	4	5310
12	13490	5.8	0.46	245	30	<5	0.43	49	6	101	2149	4.19	<10	0.24	40	<1	0.03	<1	560	254	140	<20	21	<0.01	<10	2	<10	3	>10000
13	13491	>30	1.57	640	45	<5	0.22	49	8	28	6167	3.58	<10	1.78	215	<1	0.05	7	690	4614	285	<20	16	<0.01	<10	4	<10	3	9889
14	13492	3.7	0.63	65	45	<5	0.61	39	5	109	790	2.08	<10	0.40	140	3	0.05	2	380	62	35	<20	25	<0.01	<10	2	<10	3	8716
15	13493	4.9	1.37	80	45	<5	0.69	92	8	66	8325	5.23	10	1.33	257	1	0.06	<1	710	48	5	<20	22	<0.01	<10	2	<10	3	>10000
16	13494	>30	0.15	2065	40	<5	0.15	889	6	25	>10000	5.70	10	0.18	30	<1	0.02	<1	780	>10000	1255	<20	33	<0.01	<10	6	<10	3	>10000
17	13495	4.8	1.45	40	50	<5	0.39	50	8	59	6120	4.43	10	1.73	290	<1	0.04	2	550	110	<5	<20	19	<0.01	<10	2	<10	3	>10000
18	13496	>30	0.39	605	30	<5	0.29	264	8	42	3648	5.10	10	0.19	<1	<1	0.02	<1	340	>10000	145	<20	24	<0.01	<10	1	<10	4	>10000
19	13497	>30	0.33	470	35	<5	0.15	36	4	52	1388	1.05	<10	0.09	9	1	0.02	<1	200	2400	120	<20	41	<0.01	<10	<1	<10	2	8094
20	13499	4.0	1.42	165	35	<5	1.25	<1	30	64	177	5.90	20	0.75	169	<1	0.11	11	240	106	10	<20	149	0.02	<10	60	<10	4	89
21	13500	4.8	0.64	700	15	<5	0.34	<1	22	57	173	6.71	20	0.43	<1	4	0.05	6	150	32	40	<20	21	<0.01	<10	2	<10	5	362
22	13501	23.7	0.49	730	25	<5	0.54	156	7	36	3101	4.46	10	0.26	<1	<1	0.03	<1	470	>10000	55	<20	21	<0.01	<10	<1	<10	4	>10000
23	13502	22.3	0.23	935	15	<5	0.11	117	5	82	5189	4.67	10	0.15	<1	3	0.01	<1	460	1016	30	<20	14	<0.01	<10	<1	<10	2	>10000
24	13503	19.1	0.67	930	35	<5	0.41	118	9	47	8253	6.11	20	0.35	<1	5	0.05	<1	900	2096	30	<20	12	<0.01	<10	<1	<10	4	>10000
25	13504	13.6	0.72	690	40	<5	0.35	45	7	40	3120	3.70	10	0.44	4	7	0.04	<1	590	2202	25	<20	18	<0.01	<10	<1	<10	3	>10000

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-302

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

20-Aug-03

ATTENTION: Bob Carmichael

No. of samples received: 41
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 14
Samples submitted by: Redfern

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	23509	0.39	0.011					
2	23510	0.26	0.008	4.8	0.14	0.20	0.01	7.05
3	23511	0.38	0.011	4.7	0.14	0.21	0.01	2.51
4	23512	<0.03	<0.001					
5	23513	0.18	0.005					
6	23514	0.37	0.011					
7	23515	0.30	0.009					
8	23516	0.19	0.006					
9	23517	0.40	0.012					
10A	23518A			304	8.87	1.49	10.1	14.9
10B	23518B	2.11	0.062					
13	23519	0.14	0.004					
14	23520	0.26	0.008					
15	23521	0.24	0.007					
16	23522	0.07	0.002					
17	23523	0.06	0.002					
18	23524	0.06	0.002					
19	23525	0.07	0.002					
20	23526	0.16	0.005					
21	23527	0.53	0.015					
22	23528	0.19	0.006					
23	23529	0.14	0.004					
24	23530	0.32	0.009					
25	23531	0.18	0.005					
26	23532	0.16	0.005					
27	23533	0.10	0.003					
28	23534	0.06	0.002					
29	23535	0.20	0.006					
30	23536	0.42	0.012					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
31	23537	0.49	0.014					
32	23538	0.54	0.016					
33	23539	0.18	0.005					
34	23540	0.07	0.002					
35	23541	0.20	0.006					
36	23542	<0.03	<0.001					
37	23543	0.17	0.005					
38	23544	0.10	0.003					
39	23545	0.03	0.001					
40	23546	0.14	0.004					
41	23547	0.17	0.005					
42	23548	0.04	0.001					
43	23549	0.03	0.001					
QC DATA:								
Repeat:								
1	23509	0.41	0.012					
10B	23518B	2.20	0.064					
19	23525	0.07	0.002					
21	23527	0.49	0.014					
30	23536	0.38	0.011					
31	23537	0.49	0.014					
32	23538	0.56	0.016					
36	23542	<0.03	<0.001					
Resplit:								
1	23509	0.42	0.012					
36	23542	<0.03	<0.001					
Standard:								
PM164		3.15	0.092					
PM164		3.07	0.090					
CU106				136	3.97	1.43		
PB106				58.0	1.69	0.61	0.52	0.84

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
XLS/03

20-Aug-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-302

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 41
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 14
Samples submitted by: Redfern

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	23509	8.9	0.42	140	<5	<5	2.82	<1	14	63	135	>10	10	0.37	<1	12	0.02	13	100	118	20	<10	110	<0.01	<10	2	<10	4	167
2	23510	4.3	1.98	595	<5	<5	2.50	274	21	53	1865	9.32	10	2.70	202	<1	0.04	5	240	124	15	<10	123	0.02	<10	4	<10	5	>10000
3	23511	4.5	2.34	725	<5	<5	2.34	96	20	85	2014	>10	10	3.48	257	<1	0.02	10	200	118	30	<10	96	<0.01	<10	4	<10	5	>10000
4	23512	<0.2	2.29	<5	175	<5	1.76	<1	20	89	36	3.51	10	1.33	368	3	0.25	31	930	14	<5	<10	134	0.19	<10	12	<10	6	52
5	23513	1.7	0.70	85	<5	<5	1.58	19	11	59	325	5.93	<10	0.27	<1	<1	0.05	4	380	24	10	<10	56	<0.01	<10	3	<10	6	4657
6	23514	4.6	0.88	245	<5	<5	3.62	<1	13	63	5697	>10	20	0.77	<1	<1	0.04	7	500	29	<5	<10	149	<0.01	20	1	<10	7	105
7	23515	1.5	1.11	175	<5	<5	4.45	<1	10	50	666	8.52	10	0.89	56	<1	0.05	16	540	34	<5	<10	166	<0.01	<10	3	<10	10	199
8	23516	2.2	0.83	150	<5	<5	3.57	2	20	79	83	>10	10	0.68	<1	6	0.04	26	290	41	55	<10	151	<0.01	<10	<1	<10	6	132
9	23517	5.6	0.72	145	<5	<5	1.90	<1	21	90	84	>10	10	0.37	<1	<1	0.05	10	290	43	25	<10	86	<0.01	<10	2	<10	10	33
10	23518A	>30	0.10	2005	10	<5	0.08	872	4	17	>10000	2.71	<10	<0.01	30	<1	<0.01	<1	630	>10000	1395	<10	39	<0.01	<10	<1	<10	3	>10000
13	23519	1.8	0.66	45	<5	5	2.65	<1	8	118	22	5.20	<10	0.26	9	4	0.06	8	120	23	<5	<10	130	<0.01	<10	1	<10	3	24
14	23520	4.4	0.46	105	<5	<5	2.76	<1	12	95	51	8.92	10	0.25	<1	1	0.05	9	200	27	<5	<10	131	<0.01	<10	<1	<10	4	31
15	23521	2.8	0.36	40	<5	5	0.37	<1	16	110	53	9.52	20	0.19	<1	4	0.01	3	310	47	<5	<10	<1	<0.01	<10	1	<10	8	27
16	23522	1.0	0.32	25	<5	<5	0.50	<1	9	102	626	7.13	20	0.20	7	2	0.01	4	220	14	10	<10	<1	<0.01	<10	1	<10	7	27
17	23523	0.9	0.78	5	<5	<5	0.32	<1	9	97	1849	6.63	10	0.54	82	2	0.01	4	570	8	<5	<10	<1	<0.01	<10	4	<10	8	43
18	23524	0.8	0.72	<5	<5	<5	0.32	<1	9	68	1846	6.37	10	0.54	84	<1	0.01	4	580	7	<5	<10	<1	<0.01	<10	4	<10	8	42
19	23525	1.1	0.43	10	<5	5	0.29	<1	39	113	28	>10	20	0.34	<1	<1	0.02	1	290	26	<5	<10	<1	<0.01	<10	2	<10	7	68
20	23526	2.1	0.26	20	<5	<5	0.16	<1	13	107	58	>10	20	0.20	<1	2	0.01	3	130	77	<5	<10	<1	<0.01	<10	<1	<10	5	138
21	23527	8.6	0.47	210	<5	<5	0.26	<1	33	86	1391	>10	20	0.33	<1	2	0.02	10	280	98	15	<10	<1	<0.01	<10	11	<10	5	81
22	23528	2.9	0.61	85	<5	<5	0.62	<1	100	108	166	>10	20	0.35	<1	4	0.05	14	530	42	<5	<10	2	<0.01	<10	22	<10	7	89
23	23529	0.8	0.61	75	<5	<5	0.42	<1	112	94	102	>10	20	0.45	<1	<1	0.03	20	610	23	<5	<10	3	<0.01	<10	18	<10	6	175
24	23530	3.1	0.24	205	<5	<5	0.36	<1	50	150	2332	>10	20	0.24	<1	5	0.01	8	380	21	10	<10	<1	<0.01	<10	2	<10	5	185
25	23531	0.4	0.24	100	<5	<5	0.23	<1	47	136	81	>10	10	0.20	<1	2	0.01	5	440	14	5	<10	<1	<0.01	<10	1	<10	6	68
26	23532	0.9	0.28	205	<5	<5	0.29	<1	47	116	88	>10	20	0.21	<1	6	0.01	6	650	13	<5	<10	<1	<0.01	<10	2	<10	6	37
27	23533	0.9	0.38	35	<5	<5	0.40	<1	58	129	197	>10	20	0.28	<1	<1	0.03	6	380	12	<5	<10	1	<0.01	<10	2	<10	7	19

REDFERN RESOURCES LTD. ICP CERTIFICATE OF ANALYSIS AK 2003-302 ECO TECH LABORATORY LTD.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
28	23534	0.8	0.64	90	<5	<5	0.42	<1	24	111	74	5.17	<10	0.31	10	9	0.03	11	730	16	5	<10	7	0.01	<10	3	<10	6	101
29	23535	7.8	0.40	185	<5	<5	0.25	<1	25	105	54	8.51	10	0.18	<1	4	0.01	5	580	51	<5	<10	<1	<0.01	<10	2	<10	4	79
30	23536	6.2	0.32	300	5	<5	0.25	<1	22	120	41	6.14	<10	0.12	<1	5	0.01	6	750	65	<5	<10	<1	<0.01	<10	<1	<10	4	114
31	23537	5.4	0.35	250	<5	<5	0.22	<1	22	115	43	6.47	10	0.12	<1	5	0.01	5	660	43	5	<10	<1	<0.01	<10	1	<10	4	53
32	23538	5.9	0.29	305	<5	<5	0.22	<1	24	105	45	7.20	10	0.12	<1	7	0.01	6	680	47	<5	<10	<1	<0.01	<10	<1	<10	4	58
33	23539	1.2	0.24	50	25	<5	0.10	<1	8	96	26	2.59	<10	0.05	<1	3	<0.01	2	190	14	<5	<10	<1	<0.01	<10	<1	<10	2	96
34	23540	0.5	0.27	25	20	<5	0.10	<1	5	136	75	2.97	<10	0.06	<1	6	<0.01	4	210	10	5	<10	<1	<0.01	<10	<1	<10	3	80
35	23541	0.9	0.23	90	<5	<5	0.12	<1	11	113	136	3.64	<10	0.06	<1	4	<0.01	3	200	24	25	<10	<1	<0.01	<10	<1	<10	2	213
36	23542	0.2	2.11	<5	115	<5	1.87	<1	22	98	37	3.54	10	1.24	400	5	0.23	34	1110	22	<5	<10	116	0.19	<10	8	<10	7	56
37	23543	0.9	0.35	110	<5	<5	0.17	<1	17	104	22	4.49	<10	0.12	9	4	<0.01	6	300	19	<5	<10	3	<0.01	<10	2	<10	3	28
38	23544	1.1	0.47	70	<5	<5	0.96	<1	25	136	70	7.57	10	0.41	408	7	<0.01	10	440	13	25	<10	25	<0.01	<10	6	<10	5	31
39	23545	0.1	1.44	35	<5	5	1.08	<1	38	91	18	8.68	10	1.49	961	<1	<0.01	12	1240	9	5	<10	27	0.02	<10	56	<10	8	65
40	23546	0.5	0.40	45	<5	<5	0.08	<1	28	126	191	>10	20	0.34	<1	3	<0.01	4	270	15	<5	<10	<1	<0.01	<10	3	<10	4	115
41	23547	2.9	2.33	90	<5	<5	0.27	<1	37	115	484	>10	30	2.39	942	<1	0.01	7	670	19	<5	<10	12	0.03	<10	56	<10	5	160
42	23548	0.1	3.32	30	40	<5	0.30	<1	31	75	181	7.30	10	3.01	1270	<1	0.01	17	990	10	<5	<10	4	0.07	<10	66	<10	4	121
43	23549	<0.2	2.67	15	20	<5	0.34	<1	26	71	213	7.88	10	3.05	1602	<1	0.02	11	880	7	5	<10	8	0.03	<10	76	<10	5	108
QC DATA:																													
Resplit:																													
1	23509	8.8	0.39	195	<5	5	2.85	<1	18	72	165	>10	20	0.36	<1	11	0.02	15	130	117	30	<10	111	<0.01	<10	1	<10	5	187
36	23542	0.2	2.03	<5	115	<5	1.83	<1	25	94	33	3.55	10	1.21	379	3	0.21	32	1160	20	5	<10	108	0.17	<10	11	<10	7	57
Repeat:																													
1	23509	8.7	0.29	185	<5	5	2.94	<1	14	54	131	>10	10	0.33	<1	11	<0.01	18	110	117	45	<10	100	<0.01	<10	3	<10	4	180
10	23518A	>30	0.13	2000	<5	<5	0.12	992	4	23	>10000	3.88	<10	0.12	43	<1	0.01	<1	720	>10000	1295	<10	34	<0.01	<10	5	<10	2	>10000
19	23525	1.0	0.42	5	<5	<5	0.30	<1	40	113	25	>10	20	0.34	<1	<1	0.02	2	310	26	<5	<10	<1	<0.01	<10	2	<10	6	23
36	23542	0.2	2.13	<5	110	<5	1.87	<1	22	100	39	3.69	10	1.27	399	5	0.22	33	1220	20	<5	<10	112	0.18	<10	17	<10	7	59
Standard:																													
GEO '03		1.5	1.68	60	140	<5	1.63	<1	20	60	88	3.85	10	0.91	626	<1	0.03	29	930	20	<5	<10	45	0.11	<10	65	<10	10	72
GEO '03		1.6	1.74	55	140	<5	1.67	1	20	60	89	3.95	10	0.91	637	2	0.03	30	970	20	<5	<10	41	0.12	<10	63	<10	8	76

JJ/kk
df/290
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-315

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

26-Aug-03

ATTENTION: Bob Carmichael

No. of samples received: 64
Sample type: Rock
Project #: Tulsequah Chief
Shipment #: 17
Samples submitted by: T.Z.

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	23651	0.04	0.001					
2	23652A	2.11	0.062					
2	23652B			142	4.14	0.61	0.43	1.02
3	23653	0.06	0.002					
4	23654	0.05	0.001					
5	23655	0.03	0.001					
6	23657	<0.03	<0.001					
7	23658	<0.03	<0.001					
8	23659	0.11	0.003					
9	23660	<0.03	<0.001					
10	23661	<0.03	<0.001					
11	23662	0.14	0.004					
12	23663	<0.03	<0.001					
13	23664	<0.03	<0.001					
14	23665	<0.03	<0.001					
15	23666	<0.03	<0.001					
16	23667	<0.03	<0.001					
17	23668	<0.03	<0.001					
18	23669	<0.03	<0.001					
19	23670	0.03	0.001					
20	23671	0.05	0.001					
21	23672	0.11	0.003	2.1	0.06	0.06	0.01	2.61
22	23673	<0.03	<0.001					
23	23674	<0.03	<0.001					
24	23675	0.30	0.009					
25	23676	0.16	0.005					
26	23677	0.12	0.003					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. AK3-315 26-Aug-03

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
27	23678	0.11	0.003					
28	23679	0.13	0.004					
29	23680	0.07	0.002					
30	23681	0.04	0.001					
31	23682	0.03	0.001					
32	23683	0.05	0.001					
33	23684	0.07	0.002					
34	23685	0.11	0.003					
35	23686	0.06	0.002					
36	23687	0.04	0.001					
37	23688	0.04	0.001					
38	23689	0.03	0.001					
39	23690	0.07	0.002					
40	23691A	2.04	0.059					
40	23691B			130	3.79	0.62	0.42	0.99
41	23692	0.08	0.002					
42	23693	0.04	0.001					
43	23694	2.03	0.059					
44	23695	0.09	0.003					
45	23696	0.09	0.003					
46	23697	0.18	0.005					
47	23698	0.16	0.005					
48	23699	0.05	0.001					
49	23700	0.04	0.001					
50	23701	0.05	0.001					
51	23702	0.06	0.002					
52	23703	0.08	0.002					
53	23704	0.08	0.002					
54	23705	0.09	0.003					
55	23706	0.06	0.002					
56	23707	0.08	0.002					
57	23708	0.27	0.008					
58	23709	0.29	0.008	12.2	0.36	0.02	0.02	0.09
59	23710	0.79	0.023	39.8	1.16	0.04	0.07	0.17
60	23711	6.74	0.197	382	11.14	0.88	4.87	11.9
61	23712	0.09	0.003					
62	23713	1.57	0.046	96.7	2.82	0.37	0.64	2.86
63	23714	0.37	0.011	14.5	0.42	0.06	0.06	0.43
64	23715	0.09	0.003					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. AK3-315 26-Aug-03

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
QC DATA:								
Repeat:								
1	23651	0.03	0.001					
10	23661	<0.03	<0.001					
19	23670	0.03	0.001					
36	23687	0.03	0.001					
45	23696	0.09	0.003					
54	23705	0.12	0.003					
59	23710	0.80	0.023					
60	23711	7.34	0.214					
61	23712	0.12	0.003					
62	23713	1.49	0.043					
63	23714	0.35	0.010					
64	23715	0.07	0.002					
Reaplit:								
1	23651	0.04	0.001					
Standard:								
PB106				58.3	1.70	0.63	0.49	0.85
PM164		3.11	0.091					
PM164		3.08	0.090					

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

26-Aug-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-315

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 64
Sample type: Rock
Project #: Tulsequah Chief
Shipment #: 17
Samples submitted by: T.Z.

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	23651	1.6	2.80	35	25	<5	4.98	<1	56	69	253	>10	10	0.40	3139	<1	0.17	38	253	200	<5	<20	4	0.02	<10	26	<10	4	386
2	23652	>30	1.04	465	25	<5	0.18	42	6	22	5935	3.82	<10	1.25	157	<1	0.03	5	484	4134	230	<20	13	<0.01	<10	2	<10	2	>10000
3	23653	0.7	3.65	10	25	5	3.02	<1	36	58	109	7.86	<10	0.40	1121	<1	0.18	20	671	72	5	<20	4	0.03	<10	43	<10	5	94
4	23654	1.7	3.28	45	25	<5	3.06	2	72	55	285	9.93	<10	0.47	1583	<1	0.19	45	506	144	20	<20	26	0.02	<10	51	<10	5	755
5	23655	1.5	0.98	35	10	<5	0.79	<1	45	43	119	8.77	<10	0.17	219	<1	0.05	19	572	104	5	<20	1	<0.01	<10	13	<10	5	97
6	23657	0.7	1.13	20	15	<5	0.65	<1	39	29	91	6.36	<10	0.18	207	<1	0.09	13	627	80	5	<20	8	<0.01	<10	14	<10	4	201
7	23658	1.3	0.60	45	10	<5	0.35	<1	39	32	120	7.22	<10	0.14	110	<1	0.03	15	429	324	10	<20	2	<0.01	<10	11	<10	4	520
8	23659	10.2	2.48	75	<5	<5	4.10	19	129	77	911	>10	20	0.49	2305	<1	0.14	77	77	6376	15	<20	<1	0.02	<10	38	<10	4	6579
9	23660	0.9	2.10	110	25	<5	1.21	6	39	47	119	8.33	<10	0.36	404	12	0.15	39	484	176	115	<20	13	0.01	<10	34	<10	5	244
10	23661	0.4	1.27	30	35	<5	0.75	<1	38	29	114	6.44	<10	0.18	157	<1	0.09	11	649	50	5	<20	10	<0.01	<10	14	<10	4	76
11	23662	2.5	4.24	90	<5	<5	2.72	<1	57	91	333	>10	20	0.56	700	<1	0.22	40	143	860	10	<20	14	0.02	<10	54	<10	7	93
12	23663	0.7	1.52	25	30	<5	0.75	<1	39	34	122	7.40	<10	0.20	136	<1	0.10	19	187	126	15	<20	14	<0.01	<10	17	<10	4	56
13	23664	0.6	4.10	15	30	<5	2.12	<1	36	59	115	7.43	<10	0.95	987	<1	0.26	18	770	76	<5	<20	8	0.03	<10	70	<10	5	238
14	23665	0.5	2.72	30	35	<5	1.35	2	37	40	98	7.71	<10	0.68	691	<1	0.17	20	649	440	10	<20	19	0.02	<10	39	<10	4	875
15	23666	0.8	2.32	15	35	<5	1.22	<1	38	39	116	7.25	<10	0.55	558	<1	0.16	18	616	310	10	<20	16	<0.01	<10	32	<10	4	339
16	23667	<0.2	2.24	80	120	<5	1.25	4	14	83	48	4.36	<10	1.56	397	15	0.19	45	1089	22	90	<20	88	0.10	<10	83	<10	6	46
17	23668	1.0	3.40	20	45	<5	1.34	2	39	37	133	5.86	<10	1.47	1239	<1	0.17	17	902	336	15	<20	16	0.04	<10	65	<10	5	691
18	23669	0.8	2.70	50	40	<5	1.15	2	39	53	112	8.79	<10	1.28	933	<1	0.15	16	836	176	10	<20	16	0.04	<10	52	<10	6	761
19	23670	0.4	3.43	35	20	<5	1.46	4	39	59	122	9.05	<10	1.50	1222	<1	0.20	18	869	112	10	<20	19	0.06	<10	63	<10	7	998
20	23671	1.6	0.73	35	15	<5	0.74	1	39	43	129	9.37	<10	0.24	219	<1	0.04	18	319	196	5	<20	5	<0.01	<10	14	<10	6	650
21	23672	2.0	0.62	135	<5	<5	0.47	98	33	87	496	>10	10	0.47	128	<1	0.03	11	253	86	<5	<20	6	<0.01	<10	12	<10	7	>10000
22	23673	<0.2	5.95	30	25	<5	1.34	<1	38	80	118	8.09	<10	3.67	2269	<1	0.17	23	671	34	<5	<20	10	0.12	<10	174	<10	5	689
23	23674	<0.2	4.13	55	25	5	0.87	3	38	74	101	8.76	<10	2.80	1864	<1	0.12	17	759	28	<5	<20	11	0.10	<10	105	<10	6	1331
24	23675	8.9	0.89	355	<5	<5	1.55	<1	24	94	1524	>10	10	0.42	614	<1	0.04	12	330	42	25	<20	<1	<0.01	<10	12	<10	7	485
25	23676	5.0	0.55	170	<5	<5	0.29	<1	36	81	512	>10	10	0.33	<1	<1	0.03	11	275	38	25	<20	5	<0.01	<10	10	<10	7	40

REDFERN RESOURCES LTD. ICP CERTIFICATE OF ANALYSIS AK 2003-315 ECO TECH LABORATORY LTD.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	23677	3.9	0.95	165	<5	<5	0.46	<1	28	78	868	>10	10	0.61	160	<1	0.04	13	429	40	15	<20	8	<0.01	<10	15	<10	7	52
27	23678	2.4	1.50	160	<5	<5	0.33	<1	45	75	782	>10	10	1.29	632	<1	0.04	20	495	38	15	<20	7	0.01	<10	30	<10	8	90
28	23679	2.1	2.21	115	10	<5	0.47	<1	33	65	530	>10	10	1.77	1033	<1	0.05	14	484	42	5	<20	9	0.02	<10	47	<10	7	95
29	23680	1.1	1.75	80	<5	<5	0.36	<1	38	40	157	10.17	<10	1.34	977	<1	0.04	14	539	30	<5	<20	10	0.02	<10	36	<10	5	55
30	23681	0.5	2.96	95	20	<5	0.54	<1	35	64	121	10.34	<10	2.19	1448	<1	0.07	18	594	28	5	<20	8	0.05	<10	65	<10	5	82
31	23682	0.6	3.50	60	15	<5	0.59	<1	35	55	212	8.15	<10	2.62	1418	<1	0.08	18	594	24	10	<20	9	0.06	<10	87	<10	5	117
32	23683	0.4	1.33	80	15	<5	0.43	<1	34	56	163	9.29	<10	0.82	470	<1	0.05	14	616	16	5	<20	5	0.02	<10	26	<10	5	37
33	23684	0.4	0.41	135	<5	<5	0.27	<1	39	58	473	12.59	<10	0.22	<1	<1	0.02	12	616	8	<5	<20	4	<0.01	<10	8	<10	6	20
34	23685	1.4	0.34	50	<5	<5	0.23	<1	34	40	608	9.46	<10	0.14	<1	<1	0.02	10	561	16	<5	<20	3	<0.01	<10	8	<10	5	15
35	23686	0.3	0.28	35	<5	<5	0.19	<1	34	37	907	8.68	<10	0.13	<1	<1	0.02	11	583	12	<5	<20	2	<0.01	<10	7	<10	5	19
36	23687	0.4	0.30	30	<5	<5	0.19	<1	29	46	406	7.82	<10	0.12	<1	<1	0.02	9	539	6	<5	<20	4	<0.01	<10	7	<10	5	11
37	23688	0.3	1.07	45	<5	<5	0.44	<1	34	57	286	10.33	<10	0.63	268	<1	0.05	13	671	12	5	<20	7	<0.01	<10	19	<10	6	44
38	23689	0.2	1.16	40	<5	<5	0.31	<1	29	50	86	8.15	<10	0.88	475	<1	0.03	10	594	12	5	<20	7	0.01	<10	27	<10	5	59
39	23690	1.6	0.36	95	<5	<5	0.23	<1	29	41	2832	9.17	<10	0.15	<1	<1	0.02	18	660	24	5	<20	4	<0.01	<10	9	<10	4	27
40	23691	>30	1.04	500	10	<5	0.19	44	7	23	5851	3.93	<10	1.28	164	<1	0.03	5	605	4088	245	<20	9	<0.01	<10	2	<10	3	9876
41	23692	1.5	0.59	135	<5	<5	0.28	<1	28	98	199	7.07	<10	0.44	191	3	0.02	18	407	32	10	<20	1	<0.01	<10	17	<10	5	44
42	23693	0.5	1.12	50	15	<5	0.40	<1	24	102	766	7.21	<10	1.00	545	2	0.03	19	506	24	10	<20	7	<0.01	<10	30	<10	5	105
43	23694	>30	0.08	1855	<5	<5	0.11	761	4	22	10000	5.68	<10	0.13	23	<1	<0.01	<1	616	>10000	1055	<20	4	<0.01	20	3	<10	<1	>10000
44	23695	1.3	0.28	95	<5	<5	0.17	<1	38	60	160	9.84	<10	0.15	<1	<1	0.02	23	385	32	25	<20	3	<0.01	<10	9	<10	5	19
45	23696	0.6	0.28	115	<5	<5	0.16	<1	40	61	123	9.54	<10	0.14	<1	<1	0.01	25	528	58	15	<20	4	<0.01	<10	9	<10	5	16
46	23697	7.7	0.23	170	<5	<5	0.07	<1	35	48	100	8.78	<10	0.12	<1	<1	0.01	21	143	48	15	<20	3	<0.01	<10	8	<10	4	13
47	23698	4.7	0.24	260	<5	<5	0.15	<1	39	59	133	11.79	<10	0.15	<1	<1	<0.01	17	616	32	5	<20	2	<0.01	<10	9	<10	6	12
48	23699	0.4	0.29	70	<5	<5	0.18	<1	47	65	182	>10	<10	0.19	<1	<1	0.02	22	594	14	<5	<20	3	<0.01	<10	7	<10	6	13
49	23700	<0.2	0.24	50	<5	<5	0.23	<1	52	78	234	>10	10	0.22	<1	<1	0.01	29	968	8	<5	<20	2	<0.01	<10	7	<10	8	13
50	23701	0.3	0.20	50	<5	<5	0.13	<1	48	68	257	>10	10	0.22	<1	<1	0.01	40	495	2	<5	<20	4	<0.01	<10	6	<10	7	17
51	23702	0.2	0.26	80	<5	<5	0.31	<1	46	94	2642	>10	10	0.31	<1	<1	0.01	25	1375	<2	<5	<20	3	<0.01	<10	7	<10	8	23
52	23703	0.4	0.23	65	<5	<5	0.24	<1	32	60	616	12.47	<10	0.22	<1	<1	<0.01	17	495	4	<5	<20	5	<0.01	<10	8	<10	5	17
53	23704	0.5	0.22	75	<5	<5	0.14	<1	39	76	969	>10	10	0.23	<1	<1	<0.01	19	583	4	10	<20	3	<0.01	<10	8	<10	6	19
54	23705	0.3	0.22	70	<5	<5	0.17	<1	50	74	1191	>10	10	0.22	<1	<1	<0.01	31	671	2	5	<20	3	<0.01	<10	9	<10	6	21
55	23706	<0.2	0.20	85	<5	<5	0.11	<1	58	65	723	12.57	<10	0.18	<1	<1	<0.01	43	407	4	<5	<20	2	<0.01	<10	7	<10	5	16
56	23707	0.2	0.18	125	<5	<5	0.06	<1	48	59	228	9.51	<10	0.13	<1	<1	<0.01	39	198	6	<5	<20	1	<0.01	<10	7	<10	4	12
57	23708	0.3	0.23	120	<5	<5	0.15	<1	49	62	88	12.32	<10	0.20	<1	<1	0.01	32	187	10	5	<20	4	<0.01	<10	9	<10	5	21
58	23709	12.0	1.06	40	40	<5	1.34	5	7	61	124	2.44	<10	0.32	165	5	0.09	7	230	208	20	<20	76	0.02	<10	2	<10	3	937
59	23710	>30	0.44	70	20	<5	0.27	7	8	43	219	2.45	<10	0.14	14	4	0.04	3	240	736	65	<20	12	0.01	<10	2	<10	3	1802
60	23711	>30	0.42	875	<5	<5	0.77	617	5	51	7927	3.84	<10	0.14	98	2	0.03	1	380	>10000	1520	<20	29	0.06	<10	1	<10	3	>10000

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-321

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

26-Aug-03

ATTENTION: Bob Carmichael

No. of samples received: 62
Sample type: Core
Project #:Tulsequah
Shipment #:15
Samples submitted by: TZ

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	23550	0.19	0.006					
2	23551	0.14	0.004					
3	23552A	2.13	0.062					
3	23552B			140	4.08	0.60	0.46	0.98
4	23553	0.21	0.006					
5	23554	0.42	0.012					
6	23555	0.54	0.016					
7	23556	0.34	0.010					
8	23557	0.42	0.012					
9	23558	0.50	0.015	8.7	0.25	0.28	<0.01	1.82
10	23559	0.27	0.008					
11	23560	0.32	0.009					
12	23561	0.82	0.024					
13	23562	0.19	0.006					
14	23563	0.14	0.004					
15	23564	0.48	0.014					
16	23565	0.53	0.015					
17	23566	0.60	0.017					
18	23567	0.07	0.002					
19	23568	0.27	0.008					
20	23569	0.42	0.012					
21	23570	0.41	0.012					
22	23571	0.22	0.006					
23	23572	0.17	0.005	2.6	0.08	0.66	<0.01	3.76
24	23573	0.09	0.003	0.9	0.03	0.04	<0.01	2.83
25	23574	0.10	0.003	0.8	0.02	0.05	<0.01	3.00
26	23575	0.24	0.007					
27	23576	0.29	0.008					
28	23577	0.16	0.005					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. AK3-321 26-Aug-03

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
29	23578	0.49	0.014					
30	23579	0.16	0.005					
31	23580	0.12	0.003					
32	23581	0.19	0.006					
33	23582	0.33	0.010					
34	23583	0.21	0.006					
35	23584	0.65	0.019					
36	23585	3.46	0.101	26.6	0.78	4.96	0.02	0.27
37	23586	3.14	0.092	26.7	0.78	5.19	0.04	11.3
38	23587	1.76	0.051	18.3	0.53	1.27	0.03	3.13
39	23588	0.19	0.006					
40	23589	0.45	0.013	1.6	0.05	0.48	0.02	1.03
41	23590	0.30	0.009	5.6	0.16	0.94	0.02	3.09
42	23591A	2.17	0.063					
42	23591B			139	4.05	0.62	0.44	1.01
43	23592	0.24	0.007	4.1	0.12	0.60	0.03	2.00
44	23593	0.41	0.012	7.6	0.22	1.26	0.05	2.86
45	23594A	2.20	0.064					
45	23594B			326	9.51	1.25	9.96	12.4
46	23595	0.36	0.010	5.3	0.16	1.43	0.02	0.13
47	23596	0.68	0.020	8.4	0.25	1.02	0.02	1.21
48	23597	0.85	0.025	13.8	0.40	1.07	0.05	8.87
49	23598	1.24	0.036	8.4	0.25	1.16	0.03	4.26
50	23599	0.76	0.022	4.2	0.12	0.26	0.02	1.87
51	23600	0.40	0.012	5.1	0.15	0.27	0.01	0.95
52	23601	2.23	0.065					
53	23602	0.84	0.024					
54	23603	0.24	0.007					
55	23604	0.38	0.011					
56	23605	0.48	0.014					
57	23606	0.12	0.003					
58	23607	0.13	0.004					
59	23608	0.30	0.009					
60	23609	0.05	0.001					
61	23610	0.04	0.001					
62	23611	0.06	0.002					
QC DATA:								
Resplit:								
1	23550	0.19	0.006					
36	23585	2.93	0.085	26.6	0.776	4.96	0.02	0.27

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. AK3-321

26-Aug-03

ET #.	Tag #	Au (g/t)	Au (oz/t)			
Repeat:						
1	23550	0.19	0.006			
10	23559	0.26	0.008			
19	23568	0.26	0.008			
34	23583	0.21	0.006			
35	23584	0.65	0.019			
36	23585	3.26	0.095			
37	23586	2.82	0.082			
38	23587	1.89	0.055			
41	23590	0.30	0.009			
48	23597	0.73	0.021			
49	23598	1.12	0.033			
50	23599	0.81	0.024			
52	23601	1.96	0.057			
Standard:						
PM906		5.71	0.167			
PM906		5.32	0.155			
PM906		5.71	0.167			
PM164		3.07	0.090			
CU106				138	4.02	1.43

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

- - - 2 2003

26-Aug-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-321

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 62
Sample type: Core
Project #:Tulsequah
Shipment #:15
Samples submitted by: TZ

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	23550	1.1	0.40	15	20	<5	1.06	<1	15	71	62	8.63	10	0.37	<1	8	<0.01	3	490	86	<5	<20	70	<0.01	<10	<1	<10	6	57
2	23551	0.8	0.76	25	50	<5	2.27	<1	7	104	17	2.87	<10	0.79	58	6	<0.01	12	330	24	5	<20	119	<0.01	<10	2	<10	4	105
3	23552	>30	1.23	465	20	<5	0.24	46	9	30	5790	4.13	<10	1.34	178	<1	<0.01	6	640	4126	260	<20	14	<0.01	<10	3	<10	2	>10000
4	23553	1.3	0.89	75	35	<5	1.63	3	11	72	47	4.98	<10	1.01	46	9	<0.01	23	420	32	60	<20	77	<0.01	<10	2	<10	4	133
5	23554	6.8	0.54	250	20	<5	2.75	<1	16	95	407	>10	20	0.60	<1	2	<0.01	10	250	106	30	<20	109	<0.01	<10	<1	<10	6	181
6	23555	3.5	0.63	55	20	<5	1.40	<1	13	70	73	8.64	10	0.61	<1	1	<0.01	6	110	126	15	<20	67	<0.01	<10	<1	<10	4	512
7	23556	2.3	0.64	315	10	<5	0.98	12	16	96	1005	>10	10	0.67	<1	<1	<0.01	3	150	42	15	<20	44	<0.01	<10	<1	<10	5	4475
8	23557	2.8	0.66	295	10	<5	1.25	29	18	119	1015	9.98	10	0.55	<1	<1	<0.01	5	130	48	30	<20	49	<0.01	<10	1	<10	4	6960
9	23558	9.0	0.52	270	10	<5	0.85	63	16	113	2676	>10	20	0.56	<1	<1	<0.01	<1	130	26	20	<20	36	<0.01	<10	<1	<10	4	>10000
10	23559	3.1	0.83	75	20	<5	1.17	<1	15	96	290	>10	20	0.70	<1	3	<0.01	7	100	34	10	<20	51	<0.01	<10	1	<10	4	200
11	23560	2.6	1.47	55	10	<5	0.31	<1	22	155	472	>10	30	1.96	11	3	<0.01	8	100	74	15	<20	15	<0.01	<10	2	<10	5	499
12	23561	3.0	1.13	65	45	<5	2.18	<1	30	49	83	7.27	10	1.24	244	3	<0.01	8	140	72	5	<20	32	<0.01	<10	2	<10	11	596
13	23562	1.0	0.81	10	10	<5	0.25	<1	40	144	61	>10	20	1.11	<1	<1	<0.01	6	130	48	10	<20	11	<0.01	<10	2	<10	7	213
14	23563	0.6	0.47	10	10	10	2.16	<1	17	223	66	9.97	10	0.26	<1	6	<0.01	10	70	32	<5	40	87	<0.01	<10	1	<10	4	59
15	23564	3.3	0.90	70	20	<5	0.76	<1	20	92	74	9.97	10	0.68	<1	<1	<0.01	3	330	76	<5	<20	29	<0.01	<10	<1	<10	6	222
16	23565	1.4	0.73	45	25	<5	1.63	28	12	125	75	8.69	10	0.64	<1	<1	<0.01	6	130	22	5	<20	80	<0.01	<10	<1	<10	5	6912
17	23566	1.1	1.91	130	45	<5	4.82	3	24	82	239	>10	20	0.88	82	5	<0.01	32	210	34	65	<20	225	0.01	<10	3	<10	5	399
18	23567	0.3	2.66	<5	120	<5	1.97	<1	26	143	84	4.49	10	1.67	423	4	<0.01	47	1200	26	<5	<20	127	0.23	<10	43	<10	6	74
19	23568	1.1	1.79	105	45	<5	1.17	5	20	124	378	8.81	10	0.70	210	<1	<0.01	13	120	26	15	<20	53	<0.01	<10	4	<10	4	1429
20	23569	0.8	0.57	35	10	<5	1.40	<1	15	159	544	>10	30	0.54	<1	1	<0.01	5	290	58	10	<20	43	<0.01	<10	<1	<10	7	259
21	23570	1.0	0.61	15	5	10	1.61	<1	15	133	610	>10	20	0.54	<1	<1	<0.01	8	310	62	5	<20	41	<0.01	<10	<1	<10	8	298
22	23571	0.7	0.47	15	15	<5	1.29	<1	20	142	596	>10	20	0.43	<1	2	<0.01	7	140	34	10	<20	59	<0.01	<10	<1	<10	5	161
23	23572	2.7	0.54	20	50	<5	1.92	217	8	70	6112	5.84	<10	0.41	19	<1	<0.01	<1	470	22	<5	<20	86	<0.01	<10	<1	<10	4	>10000
24	23573	0.9	0.64	20	25	<5	1.83	112	8	115	269	5.16	<10	0.48	38	<1	<0.01	<1	380	36	<5	<20	51	<0.01	<10	<1	<10	5	>10000
25	23574	0.8	0.71	30	15	<5	1.82	123	7	94	400	3.58	<10	0.38	48	<1	<0.01	<1	350	28	15	<20	27	<0.01	<10	1	<10	4	>10000

REDFERN RESOURCES LTD. ICP CERTIFICATE OF ANALYSIS AK 2003-321 ECO TECH LABORATORY LTD.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	23575	2.3	0.54	30	15	<5	2.49	25	18	135	1874	9.95	20	0.33	<1	3	<0.01	14	430	26	20	<20	81	<0.01	<10	2	<10	6	6578
27	23576	1.6	0.32	15	5	<5	3.71	<1	19	136	1558	>10	20	0.19	<1	<1	<0.01	9	350	40	<5	<20	155	<0.01	30	3	<10	6	345
28	23577	0.9	0.46	35	55	<5	5.83	<1	9	191	389	9.41	10	0.13	<1	8	<0.01	25	130	28	25	20	242	<0.01	<10	<1	<10	4	183
29	23578	1.9	0.79	160	40	<5	8.02	<1	12	169	2175	8.99	10	0.36	199	2	<0.01	31	210	24	15	<20	291	0.02	<10	6	<10	3	152
30	23579	1.0	6.28	25	50	<5	5.25	26	37	177	1572	9.46	20	3.13	1427	<1	<0.01	56	600	40	<5	<20	118	0.21	<10	114	<10	6	4760
31	23580	0.7	5.90	20	55	<5	8.25	13	36	165	655	9.31	20	2.56	1263	<1	<0.01	60	490	46	<5	<20	120	0.17	<10	108	<10	5	3552
32	23581	1.3	0.54	15	20	<5	0.62	<1	17	84	2002	>10	20	0.26	<1	<1	<0.01	7	460	12	5	<20	17	<0.01	<10	1	<10	6	562
33	23582	1.7	0.33	45	15	<5	0.63	<1	13	71	242	9.57	20	0.15	<1	<1	<0.01	5	90	24	10	<20	36	<0.01	<10	<1	<10	4	84
34	23583	0.9	0.34	40	<5	<5	0.22	<1	8	65	56	3.26	<10	0.08	<1	4	0.02	6	110	34	<5	<20	20	<0.01	<10	<1	<10	4	34
35	23584	1.2	0.37	80	5	<5	0.19	<1	8	83	371	2.90	<10	0.08	<1	5	0.03	19	120	36	5	<20	14	<0.01	<10	1	<10	3	86
36	23585	25.1	0.36	505	<5	<5	0.47	8	10	131	>10000	>10	20	0.40	<1	<1	0.01	19	560	212	75	<20	18	<0.01	<10	2	<10	5	2760
37	23586	24.9	0.25	655	<5	<5	0.40	423	9	105	>10000	>10	20	0.29	<1	<1	<0.01	<1	540	240	35	<20	21	<0.01	<10	2	<10	4	>10000
38	23587	18.8	0.42	905	5	<5	0.25	168	18	60	>10000	6.15	<10	0.16	<1	7	0.03	11	540	114	125	<20	12	<0.01	<10	1	<10	6	>10000
39	23588	1.6	0.35	145	<5	<5	0.19	<1	7	125	2779	4.16	<10	0.14	<1	4	0.04	27	220	138	10	<20	12	<0.01	<10	2	<10	4	397
40	23589	1.8	0.50	45	20	<5	0.35	44	9	58	4792	6.83	10	0.29	<1	<1	<0.01	4	410	190	10	<20	7	<0.01	<10	2	<10	3	>10000
41	23590	5.4	0.30	270	15	<5	0.14	125	13	63	8877	7.91	10	0.19	<1	<1	<0.01	<1	370	230	60	<20	5	<0.01	<10	1	<10	3	>10000
42	23591	>30	1.34	420	35	<5	0.23	45	8	29	6438	3.85	<10	1.45	182	<1	<0.01	7	510	3614	245	<20	18	<0.01	<10	3	<10	2	>10000
43	23592	4.2	0.38	300	20	<5	0.22	77	12	86	5420	5.56	10	0.21	<1	<1	<0.01	<1	180	278	60	<20	11	<0.01	<10	2	<10	2	>10000
44	23593	7.8	0.50	185	25	<5	0.31	105	16	92	>10000	>10	40	0.48	<1	6	<0.01	11	400	292	80	<20	7	<0.01	<10	3	<10	5	>10000
45	23594	>30	0.10	1475	15	<5	0.13	725	7	26	>10000	5.11	<10	0.13	30	<1	<0.01	<1	490	>10000	1005	<20	14	<0.01	<10	3	<10	2	>10000
46	23595	5.2	0.87	180	25	<5	0.49	4	15	92	>10000	7.73	20	0.54	53	2	<0.01	6	460	174	45	<20	16	0.01	<10	5	<10	4	1047
47	23596	8.1	0.75	410	30	<5	0.36	66	20	112	>10000	>10	50	0.88	<1	19	<0.01	46	280	158	205	<20	9	<0.01	<10	4	<10	4	>10000
48	23597	13.9	0.50	540	40	<5	0.48	314	8	90	>10000	9.24	30	0.48	42	<1	<0.01	<1	140	346	60	<20	17	<0.01	<10	<1	<10	2	>10000
49	23598	8.4	0.53	130	30	<5	0.33	150	12	90	>10000	>10	40	0.51	<1	5	<0.01	<1	260	226	<5	<20	8	<0.01	<10	<1	<10	4	>10000
50	23599	3.9	0.23	90	15	<5	0.30	54	17	38	2219	6.26	10	0.15	<1	<1	<0.01	<1	370	140	<5	<20	5	<0.01	<10	<1	<10	4	>10000
51	23600	4.8	0.32	205	15	<5	0.34	40	18	50	2327	7.36	20	0.13	<1	<1	<0.01	5	940	86	35	<20	4	<0.01	<10	2	<10	3	9236
52	23601	16.5	0.17	440	10	<5	0.12	4	51	151	1512	>10	50	0.30	<1	<1	<0.01	7	90	290	75	<20	4	<0.01	<10	8	<10	4	1088
53	23602	10.7	0.23	350	10	5	0.18	<1	41	133	393	>10	30	0.20	<1	2	<0.01	8	50	140	45	<20	5	<0.01	<10	9	<10	3	115
54	23603	2.3	0.23	130	<5	<5	0.07	22	51	73	92	9.88	40	<0.01	<1	13	<0.01	47	<10	<2	95	<20	<1	<0.01	<10	53	<10	18	165
55	23604	3.0	0.28	120	30	30	0.10	<1	123	104	96	>10	40	0.19	<1	2	<0.01	10	120	28	10	<20	7	<0.01	<10	14	<10	3	35
56	23605	2.9	0.25	135	30	35	0.20	<1	135	87	99	>10	60	0.25	<1	<1	<0.01	14	300	40	15	<20	6	<0.01	<10	19	<10	4	97
57	23606	0.7	0.73	50	30	5	0.43	<1	53	154	52	>10	40	0.52	<1	<1	<0.01	17	360	8	5	<20	16	<0.01	<10	17	<10	4	68
58	23607	0.3	0.20	70	20	10	0.27	<1	66	179	45	>10	50	0.25	<1	3	<0.01	3	430	2	10	<20	10	<0.01	<10	1	<10	4	102
59	23608	1.0	0.77	80	25	10	0.62	<1	73	160	52	>10	50	0.71	<1	<1	<0.01	18	360	8	15	<20	17	0.03	<10	10	<10	4	145
60	23609	<0.2	1.37	30	20	<5	0.23	<1	14	127	14	6.78	20	1.10	329	2	<0.01	5	260	4	5	<20	6	<0.01	<10	3	<10	3	62
61	23610	<0.2	1.28	35	25	5	0.22	<1	35	83	27	7.56	20	1.14	808	<1	<0.01	13	800	4	<5	<20	10	0.03	<10	35	<10	5	55
62	23611	0.2	2.07	35	35	<5	0.30	<1	31	97	111	9.43	20	1.86	1098	<1	<0.01	11	750	4	<5	<20	15	0.03	<10	50	<10	4	111

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-328

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

28-Aug-03

ATTENTION: Bob Carmichael

No. of samples received: 33
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 18
Samples submitted by: T.Z.

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	23716	<0.03	<0.001					
2	23717	0.03	0.001					
3	23718	2.08	0.061					
4	23719	<0.03	<0.001					
5	23720	<0.03	<0.001					
6	23721	<0.03	<0.001					
7	23722	0.03	0.001					
8	23723	<0.03	<0.001					
9	23724	<0.03	<0.001					
10	23725	<0.03	<0.001					
11	23726	<0.03	<0.001					
12	23727	<0.03	<0.001					
13	23728	0.03	0.001					
14	23729	0.04	0.001					
15	23730	0.03	0.001					
16	23731	<0.03	<0.001					
17	23732	0.03	0.001					
18	23733	<0.03	<0.001					
19	23734	<0.03	<0.001					
20	23735	0.15	0.004					
21	23736	0.19	0.006					
22	23737	3.78	0.110	38.9	1.13	0.03	0.18	0.38
23	23738	4.20	0.122	44.6	1.30	0.01	0.22	0.44
24	23739	0.31	0.009					
25	23740	0.04	0.001					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

28-Aug-03

ATTENTION: Bob Carmichael

Job #	ET #.	Tag #	SG g/cm^3
292	1	13479	2.77
292	2	13480	2.66
292	3	13481	2.66
292	9	13487	2.69
292	10	13488	2.79
292	11	13489	2.73
292	12	13490	2.79
292	15	13493	2.85
292	17	13495	2.81
292	18	13496	3.04
292	19	13497	2.75
292	22	13501	3.09
292	23	13502	2.79
292	24	13503	2.89
292	25	13504	2.81
292	26	13505	2.96
292	27	13506	2.68
302	2	23510	3.07
302	3	23511	3.03
314	2	23613	2.91
314	3	23614	2.98
314	4	23615	3.73
314	5	23616	2.74
314	6	23617	2.95
314	7	23618	2.78
314	9	23620	2.76

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. 28-Aug-03

Job #	ET #.	Tag #	SG g/cm^3
315	21	23672	3.39
315	58	23709	2.68
315	59	23710	2.72
315	60	23711	3.35
315	62	23713	2.84
315	63	23714	2.72
321	9	23558	3.03
321	23	23572	2.96
321	24	23573	2.80
321	25	23574	2.74
321	36	23585	3.96
321	37	23586	3.88
321	38	23587	2.90
321	40	23589	2.82
321	41	23590	2.89
321	43	23592	2.75
321	44	23593	3.12
321	46	23595	2.81
321	47	23596	3.36
321	48	23597	3.20
321	49	23598	3.16
321	50	23599	2.90
321	51	23600	3.12

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. 15-Aug-03

Eco Tech Laboratory Ltd.

SEP 9 2003

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-314

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

29-Aug-03

ATTENTION: Bob Carmichael

No. of samples received: 39
Sample type: Rock
Project #: Tulsequah Chief
Shipment #: 16
Samples submitted by: S.C.

		Metallic Assay	
		Au	Au
ET #.	Tag #	(g/t)	(oz/t)
4	23615	9.11	0.266

QC DATA:

Standard:

PM164	3.23	0.094

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
XLS/03

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-314

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

26-Aug-03

ATTENTION: Bob Carmichael

No. of samples received: 39
Sample type: Rock
Project #: Tulsequah Chief
Shipment #: 16
Samples submitted by: S.C.

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	23612	0.04	0.001					
2	23613	0.57	0.017	13.5	0.39	0.04	0.30	0.59
3	23614	1.35	0.039	130	3.79	0.88	0.15	1.33
4	23615*	18.9	0.551	348	10.15	0.77	4.08	29.3
5	23616	1.26	0.037	17.9	0.52	0.09	0.48	1.89
6	23617	2.67	0.078	34.6	1.01	0.45	1.16	5.56
7	23618	0.95	0.028	28.7	0.837	0.24	0.29	2.53
8	23619	0.14	0.004					
9	23620	0.22	0.006	13.0	0.379	0.05	0.02	0.36
10	23621	0.06	0.002					
11	23622	<0.03	<0.001					
12	23623	<0.03	<0.001					
13	23624	<0.03	<0.001					
14	23625	<0.03	<0.001					
15	23626	<0.03	<0.001					
16	23627	<0.03	<0.001					
17	23628	<0.03	<0.001					
18	23629	<0.03	<0.001					
19	23630	<0.03	<0.001					
20	23631	<0.03	<0.001					
21	23632	<0.03	<0.001					
22	23633	<0.03	<0.001					
23	23634	<0.03	<0.001					
24	23635	<0.03	<0.001					
25	23636	<0.03	<0.001					

*Note: **Metallic Gold Present, Metallic Assay To Follow.**

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. **AK3-314** 26-Aug-03

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
26	23637	<0.03	<0.001					
27	23638	<0.03	<0.001					
28	23639	<0.03	<0.001					
29	23640	<0.03	<0.001					
30	23641	<0.03	<0.001					
31	23642	<0.03	<0.001					
32	23643	<0.03	<0.001					
33	23644	<0.03	<0.001					
34	23645	<0.03	<0.001					
35	23646	<0.03	<0.001					
36	23647	<0.03	<0.001					
37	23648	0.03	0.001					
38	23649	<0.03	<0.001					
39	23650	<0.03	<0.001					
QC DATA:								
Repeat:								
1	23612	0.06	0.002					
2	23613	0.67	0.020					
3	23614	1.68	0.049					
4	23615*	8.36	0.244					
4	23615*	4.69	0.137					
5	23616	1.45	0.042					
6	23617	3.08	0.090					
7	23618	0.96	0.028					
10	23621	0.06	0.002					
19	23630	<0.03	<0.001					
36	23647	<0.03	<0.001					
Resplit:								
1	23612	<0.03	<0.001					
36	23647	<0.03	<0.001					
Standard:								
PM906		5.20	0.152					
PM906		5.56	0.162					
PB106				56.8	1.656	0.62	0.51	0.84

* Note: **Metallic Gold Present, Metallic Assay To Follow.**

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

22-Aug-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-314

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 39
Sample type: Rock
Project #: Tulsequah Chief
Shipment #: 16
Samples submitted by: S.C.

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	23612	<0.2	1.78	<5	100	5	1.34	<1	14	73	37	3.13	<10	1.17	306	<1	0.18	27	740	24	<5	<20	80	0.12	<10	72	<10	6	40
2	23613	13.2	1.81	55	10	<5	0.28	27	8	50	382	5.64	<10	1.75	142	1	0.05	9	420	2582	<5	<20	7	0.04	<10	4	<10	4	5277
3	23614	>30	0.45	60	<5	<5	0.17	54	9	79	7935	>10	<10	0.34	<1	1	0.03	5	320	1272	<5	<20	7	0.11	<10	2	<10	3	>10000
4	23615	>30	0.02	1745	10	<5	0.06	>1000	2	18	6926	0.48	<10	<0.01	30	<1	<0.01	<1	110	>10000	190	<20	23	0.03	<10	<1	<10	<1	>10000
5	23616	17.6	0.65	70	80	<5	0.23	76	6	40	833	1.38	<10	0.31	51	<1	0.04	3	210	4436	10	<20	8	0.02	<10	2	<10	3	>10000
6	23617	>30	0.80	35	50	<5	0.35	280	8	68	4133	3.70	<10	0.54	86	<1	0.04	3	250	>10000	<5	<20	18	0.05	<10	4	<10	2	>10000
7	23618	28.5	1.86	25	15	<5	1.32	116	16	93	2274	4.59	<10	0.88	88	<1	0.17	28	630	2794	10	<20	36	0.05	<10	14	<10	3	>10000
8	23619	2.6	2.82	10	45	<5	2.04	<1	28	235	188	2.91	<10	2.53	209	1	0.20	108	1810	70	<5	<20	76	0.09	<10	68	<10	3	265
9	23620	12.6	4.01	30	30	<5	2.96	18	12	148	473	3.01	<10	1.16	158	1	0.32	53	660	284	35	<20	62	0.06	<10	29	<10	2	3178
10	23621	1.0	1.54	15	145	<5	0.31	<1	5	45	38	1.56	<10	0.83	127	1	0.09	7	240	28	<5	<20	18	0.02	<10	5	<10	3	100
11	23622	<0.2	0.72	10	40	<5	0.22	<1	3	49	12	2.19	<10	0.32	122	2	0.05	3	260	12	<5	<20	11	0.01	<10	3	<10	2	37
12	23623	<0.2	0.63	15	10	<5	0.19	<1	6	42	26	4.57	<10	0.33	82	2	0.05	5	220	18	<5	<20	4	0.02	<10	3	<10	3	51
13	23624	0.3	0.67	30	5	<5	0.17	<1	8	54	31	5.59	<10	0.34	71	<1	0.04	6	300	24	<5	<20	11	<0.01	<10	3	<10	4	58
14	23625	<0.2	0.95	10	40	<5	0.38	<1	6	71	9	1.70	<10	0.41	174	3	0.07	5	320	18	<5	<20	13	<0.01	<10	4	<10	3	61
15	23626	<0.2	1.02	20	30	<5	0.26	<1	11	52	23	2.70	<10	0.58	221	1	0.06	5	480	16	<5	<20	14	<0.01	<10	4	<10	4	74
16	23627	<0.2	0.72	25	10	<5	0.14	<1	11	58	32	3.77	<10	0.39	101	2	0.04	6	280	14	<5	<20	6	<0.01	<10	3	<10	3	33
17	23628	<0.2	1.56	20	45	<5	0.21	<1	8	46	27	1.90	<10	1.02	337	2	0.06	10	190	24	<5	<20	9	<0.01	<10	8	<10	2	55
18	23629	<0.2	1.31	15	75	<5	0.12	<1	5	57	25	1.39	<10	0.94	309	3	0.04	9	260	20	<5	<20	9	<0.01	<10	4	10	3	58
19	23630	<0.2	0.88	10	65	<5	0.21	<1	7	48	12	1.08	<10	0.49	242	3	0.04	4	430	14	<5	<20	10	<0.01	<10	2	<10	4	50
20	23631	<0.2	0.61	15	5	<5	0.17	<1	6	42	26	4.21	<10	0.33	111	<1	0.03	4	440	12	<5	<20	6	<0.01	<10	3	<10	4	43
21	23632	<0.2	0.60	20	10	<5	0.19	<1	7	60	28	4.55	<10	0.34	97	<1	0.02	6	580	14	<5	<20	7	<0.01	<10	4	<10	5	51
22	23633	<0.2	0.73	5	25	<5	0.31	<1	7	49	8	2.03	<10	0.37	264	2	0.04	8	180	16	<5	<20	8	<0.01	<10	3	<10	4	54
23	23634	0.2	1.02	20	15	<5	0.36	<1	10	40	31	4.12	<10	0.60	327	<1	0.06	10	410	20	<5	<20	11	<0.01	<10	7	<10	4	69
24	23635	0.5	1.21	30	<5	<5	0.49	<1	15	57	40	6.47	<10	0.72	377	<1	0.08	13	470	30	<5	<20	10	<0.01	<10	12	10	5	84
25	23636	0.4	0.61	40	5	<5	0.32	<1	16	55	31	5.54	<10	0.29	133	<1	0.05	9	610	28	<5	<20	7	<0.01	<10	6	<10	8	63

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	23637	0.4	0.34	65	15	<5	0.26	<1	15	46	42	4.58	<10	0.09	14	<1	0.02	5	750	26	<5	<20	5	<0.01	<10	3	<10	7	116
27	23638	0.4	0.34	100	10	<5	0.26	<1	15	50	48	5.12	<10	0.10	10	<1	0.02	5	790	26	<5	<20	5	<0.01	<10	4	<10	7	132
28	23639	0.3	0.36	40	25	<5	0.38	<1	11	43	38	3.38	<10	0.08	66	<1	0.02	5	810	28	<5	<20	4	<0.01	<10	3	<10	6	58
29	23640	5.9	0.58	225	<5	<5	0.35	<1	85	34	466	5.45	<10	0.09	48	<1	0.06	35	520	72	30	<20	17	<0.01	<10	11	10	5	318
30	23641	3.9	1.71	70	40	<5	1.30	<1	47	75	319	2.26	<10	0.16	464	3	0.19	33	280	84	30	<20	17	0.01	<10	20	<10	3	292
31	23642	0.4	2.21	10	135	5	1.89	<1	26	90	48	3.61	10	1.37	392	2	0.23	33	1010	36	<5	<20	122	0.17	<10	24	<10	8	62
32	23643	1.6	1.50	45	15	<5	1.07	<1	41	42	149	5.54	<10	0.17	240	<1	0.17	17	380	142	15	<20	25	<0.01	<10	23	<10	5	211
33	23644	1.3	1.82	90	10	<5	1.26	<1	42	44	140	6.88	<10	0.23	309	<1	0.22	21	780	88	5	<20	16	0.01	<10	28	<10	8	126
34	23645	1.8	2.15	85	5	<5	2.68	<1	41	55	258	7.90	<10	0.25	980	<1	0.20	24	750	104	20	<20	15	0.03	<10	28	<10	7	342
35	23646	0.7	3.41	45	20	<5	3.67	<1	40	49	104	5.52	<10	0.32	1359	<1	0.30	23	810	88	10	<20	27	0.08	<10	50	<10	8	94
36	23647	0.8	3.02	65	10	5	2.81	<1	35	57	121	5.68	<10	0.33	1343	3	0.36	22	1260	120	30	<20	31	0.07	<10	62	<10	4	111
37	23648	0.6	2.91	30	15	<5	3.15	<1	38	53	101	5.82	<10	0.37	1542	<1	0.27	24	920	84	<5	<20	20	0.07	<10	43	<10	8	84
38	23649	0.5	3.25	30	<5	15	3.17	<1	34	65	129	6.08	<10	0.47	1529	<1	0.28	24	750	70	<5	<20	3	0.08	<10	54	<10	7	96
39	23650	0.5	2.32	35	<5	<5	1.77	<1	33	37	77	6.33	<10	0.28	820	<1	0.23	23	610	72	5	<20	21	0.06	<10	24	<10	8	84
QC DATA:																													
Resplit:																													
1	23612	0.2	1.79	5	100	<5	1.38	<1	17	79	34	3.22	<10	1.16	314	6	0.18	29	770	28	<5	<20	81	0.28	<10	55	<10	5	44
36	23647	0.8	3.25	55	<5	<5	3.11	<1	36	51	120	5.89	<10	0.37	1372	1	0.35	26	1210	124	20	<20	20	0.07	<10	64	<10	8	116
Repeat:																													
1	23612	0.2	1.80	5	100	<5	1.36	<1	14	76	38	3.22	<10	1.17	315	3	0.18	29	780	28	<5	<20	80	0.16	<10	59	<10	6	46
10	23621	1.1	1.83	30	80	<5	0.35	<1	6	50	41	1.74	<10	0.94	147	<1	0.10	7	310	32	<5	<20	26	<0.01	<10	4	<10	5	112
19	23630	<0.2	0.86	15	70	<5	0.20	<1	7	47	13	1.05	<10	0.48	239	3	0.04	5	430	14	<5	<20	11	<0.01	<10	2	<10	4	50
Standard:																													
GEO '03		1.6	1.56	55	140	5	1.57	<1	19	57	85	3.43	<10	0.92	611	2	0.02	28	640	22	<5	<20	36	0.09	<10	58	<10	8	68
GEO '03		1.7	1.40	55	145	<5	1.55	<1	21	57	90	3.70	10	0.86	584	1	0.02	32	700	20	<5	<20	41	0.09	<10	57	<10	11	69

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
df/314
XLS/03

SEP 19 2003

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-363

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

12-Sep-03

ATTENTION: Bob Carmichael

No. of samples received: 28
Sample type: Rock
Project #: Tulsequah Chief
Shipment #: 20
Samples submitted by: Shane

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	23827	0.19	0.006
2	23828	0.18	0.005
3	23829	0.21	0.006
4	23830	0.25	0.007
5	23831	0.19	0.006
6	23832	0.17	0.005
7	23833	0.21	0.006
8	23834	0.14	0.004
9	23835	0.21	0.006
10	23836	0.56	0.016
11	23837	0.14	0.004
12	23838	0.16	0.005
13	23839	0.09	0.003
14	23840	0.24	0.007
15	23841	0.15	0.004
16	23842	<0.03	<0.001
17	23843	0.08	0.002
18	23844	0.15	0.004
19	23845	0.24	0.007
20	23846	0.13	0.004
21	23847	0.20	0.006
22	23848	0.17	0.005
23	23849	0.10	0.003
24	23850	0.09	0.003
25	23851	0.05	0.001
26	23852	2.20	0.064
27	23853	0.06	0.002
28	23854	0.12	0.003

ECO-TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. **AK3-363** 12-Sep-03

ET #.	Tag #	Au (g/t)	Au (oz/t)
QC DATA:			
Repeat:			
1	23827	0.19	0.006
10	23836	0.57	0.017
19	23845	0.21	0.006
Resplit:			
1	23827	0.19	0.006
Standard:			
PM906		5.57	0.162

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
XLS/03

12-Sep-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-363

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 28
Sample type: Rock
Project #: Tulsequah Chief
Shipment #: 20
Samples submitted by: Shane

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	23827	1.1	0.49	100	20	<5	0.58	3	11	50	178	4.66	20	0.16	53	1	0.01	2	1510	46	70	<20	55	<0.01	<10	1	<10	5	799
2	23828	1.9	0.40	115	15	<5	0.42	5	10	69	403	3.78	20	0.11	51	41	0.01	<1	1490	64	135	<20	24	<0.01	<10	1	<10	6	1322
3	23829	1.1	0.42	110	25	<5	0.53	23	10	55	270	2.92	20	0.16	133	9	0.01	<1	1490	48	65	<20	24	<0.01	<10	<1	<10	8	5688
4	23830	0.8	0.56	110	35	<5	0.72	31	11	58	253	3.42	30	0.22	166	<1	0.02	<1	1580	40	45	<20	29	<0.01	<10	<1	<10	8	7465
5	23831	0.2	2.44	<5	115	10	0.16	<1	25	62	105	>10	80	2.10	859	<1	0.02	17	1640	72	<5	<20	43	0.14	<10	129	<10	12	191
6	23832	0.7	0.79	140	25	<5	0.70	13	10	46	232	3.03	10	0.33	356	1	0.02	2	1570	18	35	<20	30	0.03	<10	<1	<10	13	3541
7	23833	0.8	0.73	105	15	<5	0.70	19	10	76	320	3.82	10	0.27	268	<1	0.04	1	1530	12	25	<20	54	0.02	<10	<1	<10	8	5294
8	23834	0.5	0.45	100	10	<5	0.57	12	8	50	231	2.99	<10	0.20	182	6	0.02	1	1490	14	15	<20	34	<0.01	<10	<1	<10	6	3485
9	23835	0.9	0.47	195	10	<5	0.52	<1	8	89	844	5.15	10	0.18	76	4	0.02	2	1330	18	100	<20	42	<0.01	<10	<1	<10	5	391
10	23836	5.2	0.51	830	10	<5	0.48	<1	8	101	7759	7.18	20	0.23	64	5	<0.01	2	1290	32	1135	<20	24	<0.01	<10	<1	<10	4	917
11	23837	0.4	0.61	115	5	<5	0.58	<1	11	89	224	6.39	10	0.24	94	12	<0.01	3	1540	14	35	<20	50	<0.01	<10	<1	<10	6	107
12	23838	0.6	0.57	135	10	<5	0.60	<1	11	63	539	6.11	10	0.24	104	11	<0.01	2	1520	14	55	<20	50	<0.01	<10	<1	<10	6	313
13	23839	0.2	1.02	75	30	<5	0.58	<1	9	50	61	3.24	<10	0.65	337	3	0.02	4	1500	10	15	<20	25	0.05	<10	<1	<10	7	52
14	23840	1.3	0.68	130	15	<5	0.30	<1	11	79	1257	7.12	20	0.60	113	<1	<0.01	3	1140	6	15	<20	9	0.03	<10	<1	<10	6	60
15	23841	1.6	0.53	160	5	<5	0.28	<1	8	124	2437	7.02	20	0.31	72	3	<0.01	4	1290	6	15	<20	6	0.01	<10	<1	<10	6	53
16	23842	<0.2	1.87	<5	150	<5	1.39	<1	20	85	37	3.25	10	1.10	288	4	0.21	28	880	26	<5	<20	94	0.16	<10	34	<10	9	42
17	23843	0.2	0.28	80	10	<5	0.28	<1	8	68	123	5.14	10	0.14	23	1	<0.01	2	1190	10	10	<20	9	<0.01	<10	<1	<10	5	15
18	23844	0.3	0.29	65	5	<5	0.29	<1	10	67	20	5.97	10	0.14	2	<1	<0.01	<1	1280	14	<5	<20	8	<0.01	<10	<1	<10	5	46
19	23845	0.5	0.28	85	5	<5	0.31	<1	9	110	32	9.66	20	0.18	<1	<1	<0.01	3	1200	6	<5	<20	8	<0.01	<10	1	<10	5	54
20	23846	0.5	0.30	80	5	<5	0.36	<1	9	69	15	6.49	10	0.14	<1	<1	<0.01	1	1400	6	<5	<20	5	<0.01	<10	1	<10	5	43
21	23847	0.5	0.33	90	<5	<5	0.33	<1	9	107	18	6.11	10	0.12	<1	2	<0.01	3	1230	6	5	<20	6	<0.01	<10	2	<10	5	26
22	23848	0.4	0.28	85	5	<5	0.35	<1	8	66	24	5.23	10	0.11	13	<1	<0.01	<1	1310	6	5	<20	5	<0.01	<10	1	<10	5	220
23	23849	0.2	0.40	85	5	<5	0.41	2	9	68	39	4.77	10	0.17	85	<1	0.01	2	1340	8	5	<20	12	<0.01	<10	<1	<10	5	979
24	23850	0.2	0.49	70	15	<5	0.42	8	8	89	66	4.02	10	0.16	137	<1	0.01	2	1440	6	15	<20	7	<0.01	<10	1	<10	5	2574
25	23851	<0.2	0.68	60	15	<5	0.51	<1	9	96	27	3.23	<10	0.20	182	12	0.02	3	1430	12	5	<20	18	<0.01	<10	1	<10	6	553

REDFERN RESOURCES LTD. ICP CERTIFICATE OF ANALYSIS AK 2003-363 ECO TECH LABORATORY LTD.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	23852	>30	1.51	560	15	<5	0.21	38	7	27	6352	3.49	<10	1.70	218	<1	0.04	7	500	4416	220	<20	20	<0.01	<10	3	<10	2	9693
27	23853	<0.2	0.54	55	10	<5	0.42	3	12	75	64	3.47	<10	0.18	161	<1	0.01	2	1440	12	20	<20	11	<0.01	<10	<1	<10	6	1233
28	23854	0.2	0.40	70	10	<5	0.39	11	9	94	116	3.36	<10	0.12	100	2	0.01	2	1390	10	25	<20	10	<0.01	<10	1	<10	5	3275
QC DATA:																													
Resplit:																													
1	23827	1.0	0.57	105	10	<5	0.61	2	11	65	200	4.75	10	0.16	61	2	0.02	3	1540	50	70	<20	55	<0.01	<10	<1	<10	6	1082
Repeat:																													
1	23827	1.1	0.50	100	5	<5	0.59	2	11	52	178	4.73	10	0.15	53	1	0.01	2	1510	46	65	<20	53	<0.01	<10	<1	<10	5	803
10	23836	4.9	0.53	875	10	<5	0.48	<1	8	104	7853	7.54	20	0.23	59	5	0.01	3	1300	30	1155	<20	24	<0.01	<10	<1	<10	5	940
19	23845	0.6	0.29	85	<5	<5	0.32	<1	8	108	27	8.42	20	0.17	<1	<1	<0.01	3	1220	6	<5	<20	7	<0.01	<10	2	<10	5	52
27	23853	<0.2	0.55	60	10	<5	0.41	3	12	75	64	3.45	<10	0.18	161	<1	0.01	3	1410	10	15	<20	11	<0.01	<10	<1	<10	6	1222
Standard:																													
GEO '03		1.5	1.70	55	135	<5	1.64	<1	20	61	86	3.63	10	0.98	624	<1	0.03	30	730	22	<5	<20	43	0.10	<10	61	<10	11	74

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
df/351
XLS/03

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-365

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

19-Sep-03

ATTENTION: Bob Carmichael

No. of samples received: 78
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 19
Samples submitted by: Redfern

ET #.	Tag #		Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	23749		0.22	0.006	12.2	0.36	0.03	0.08	0.32
2	23750		0.16	0.005	8.1	0.24	0.03	0.10	0.28
3	23751		2.78	0.081	72.1	2.10	0.20	0.62	1.37
4	23752		2.21	0.064	138	4.02	0.65	0.47	1.02
5	23753		1.19	0.035	56.8	1.66	0.29	0.83	2.96
6	23754		2.07	0.060	50.1	1.46	0.49	0.57	4.38
7	23755		2.90	0.085	132	3.85	0.47	3.05	6.46
8	23756		1.90	0.055	74.1	2.16	1.55	0.14	1.71
9	23757		1.64	0.048	44.6	1.30	0.82	0.29	2.04
10	23758		0.76	0.022	24.3	0.71	0.23	0.57	2.00
11	23759	*	8.51	0.248	254	7.41	1.72	5.62	2.67
12	23760	*	16.35	0.477	328	9.57	2.58	2.18	22.6
13	23761	*	18.80	0.548	224	6.53	2.86	5.80	25.8
14	23762	*	4.69	0.137	220	6.42	1.58	5.56	31.6
15	23763		1.08	0.031	44.6	1.30	0.67	0.69	3.08
16	23764	*	3.96	0.115	336	9.80	1.58	5.26	26.7
17	23765		1.00	0.029	126	3.68	2.43	0.40	4.30
18	23766	*	2.80	0.082	200	5.83	13.70	0.05	3.06
19	23767		<0.03	<0.001	<0.2	<0.01	<0.01	<0.01	<0.01
20	23768	*	6.20	0.181	262	7.64	6.65	0.04	6.92
21	23769		0.86	0.025	17.6	0.51	0.76	<0.01	0.16
22	23770		0.54	0.016	16.9	0.49	0.78	<0.01	0.18
23	23771		1.74	0.051	112	3.27	3.34	0.06	0.32
24	23772		2.89	0.084	620	18.08	13.50	1.80	7.31

= Metallic Assay

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. AK3-365 19-Sep-03

ET #.	Tag #		Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
25	23773		0.69	0.020	64.3	1.88	2.69	0.08	0.30
26	23774	*	4.91	0.143	172	5.02	3.11	0.74	5.49
27	23775	*	1.95	0.057	163	4.75	3.01	0.51	4.54
28	23776		1.34	0.039	114	3.33	2.74	1.27	3.91
29	23777		1.05	0.031	109	3.18	3.04	1.03	3.46
30	23778		1.03	0.030	30.6	0.89	1.69	0.02	0.10
31	23779		1.03	0.030	18.7	0.55	1.67	0.02	0.13
32	23780	*	6.08	0.177	154	4.49	2.43	0.02	0.14
33	23781		2.66	0.078	22.1	0.65	4.56	0.14	0.75
34	23782		1.16	0.034	22.1	0.65	1.12	<0.01	0.07
35	23783		2.10	0.061	32.3	0.94	2.08	0.03	0.23
36	23784		1.26	0.037	26.8	0.78	0.69	0.35	1.22
37	23785		0.30	0.009	8.6	0.25	0.30	0.01	0.05
38	23786		1.03	0.030	7.9	0.23	0.33	0.07	0.14
39	23787	*	3.48	0.101	148	4.32	1.32	1.59	6.67
40	23788		1.11	0.032	29.9	0.87	0.39	0.22	0.90
41	23789		0.36	0.010	15.7	0.46	0.16	0.03	0.84
42	23790		0.98	0.029	36.5	1.06	0.30	0.26	1.41
43	23791		2.14	0.062	141	4.11	0.65	0.48	1.02
44	23792		1.28	0.037	50.3	1.47	0.67	0.45	2.76
45	23793		0.49	0.014	16.1	0.47	0.44	0.05	0.49
46	23794		2.16	0.063	322	9.39	1.52	10.9	14.7
47	23795		1.70	0.050	66.7	1.95	2.16	0.80	6.08
48	23796		0.89	0.026	15.5	0.45	0.06	0.11	0.17
49	23797		0.57	0.017	30.6	0.89	0.71	0.70	4.89
50	23798		0.45	0.013	34.5	1.01	0.29	0.06	1.39
51	23799		0.72	0.021	34.4	1.00	0.09	0.04	0.96
52	23800		0.07	0.002	4.2	0.12	0.01	0.07	0.06
53	23801		0.21	0.006	3.5	0.10	0.01	0.14	0.23
54	23802		0.04	0.001	0.8	0.02	<0.01	<0.01	0.02
55	23803		0.32	0.009	3.5	0.10	0.01	0.17	0.44
56	23804		0.28	0.008	2.2	0.06	0.01	0.04	0.47
57	23805		0.18	0.005	2.4	0.07	<0.01	0.06	0.13
58	23806		0.38	0.011	2.7	0.08	<0.01	0.11	0.03
59	23807		0.15	0.004	0.4	0.01	<0.01	<0.01	0.01
60	23808		0.17	0.005	3.8	0.11	<0.01	<0.01	0.01
61	23809		<0.03	<0.001	4.9	0.14	<0.01	<0.01	0.01
62	23810		<0.03	<0.001	1.5	0.04	<0.01	<0.01	0.01
63	23811		<0.03	<0.001	1.6	0.05	<0.01	<0.01	<0.01
64	23812		<0.03	<0.001	0.2	0.01	<0.01	<0.01	0.01
65	23813		<0.03	<0.001	3.5	0.10	<0.01	0.01	<0.01
66	23814		0.07	0.002	3.7	0.11	<0.01	0.01	<0.01
67	23815		0.22	0.006	4.8	0.14	<0.01	0.03	0.07
68	23816		0.21	0.006	6.1	0.18	<0.01	0.11	0.27
69	23817		0.29	0.008	8.5	0.25	0.01	0.34	0.44

** = Metallic Assay*

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. AK3-365 19-Sep-03

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
70	23818	2.11	0.062	316	9.22	1.48	10.9	14.3
71	23819	0.36	0.010	10.4	0.30	0.01	0.28	0.54
72	23820	0.57	0.017	16.3	0.48	0.01	0.10	0.26
73	23821	0.43	0.013	3.9	0.11	<0.01	0.10	0.17
74	23822	0.26	0.008	2.8	0.08	0.01	0.16	0.31
75	23823	0.16	0.005	5.2	0.15	0.27	0.18	0.85
76	23824	0.19	0.006	4.6	0.13	0.26	0.19	1.11
77	23825	0.20	0.006	7.5	0.22	0.03	0.06	0.21
78	23826	0.20	0.006	2.8	0.08	0.02	0.17	0.38

QC DATA:

Repeat:

1	23749	0.23	0.007					
2	23750	0.29	0.008					
4	23752	2.09	0.061					
10	23758	0.72	0.021					
11	23759	6.36	0.185					
12	23760	19.1	0.557					
13	23761	13.9	0.405					
14	23762	2.98	0.087					
16	23764	4.01	0.117					
18	23766	3.06	0.089					
19	23767	<0.03	<0.001					
20	23768	7.87	0.230					
24	23772	2.39	0.070					
32	23780	4.67	0.136					
36	23784	1.27	0.037					
54	23802	0.04	0.001					
71	23819	0.34	0.010					

Resplit:

1	23749	0.23	0.007					
36	23784	1.12	0.033					
71	23819	0.36	0.010					

Standard:

PM906		5.31	0.155					
CU106				138	4.02	1.43		
PB106				60.0	1.75	0.62	0.52	0.85
				60.0	1.75	0.62	0.51	0.84

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
XLS/03

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-365

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

19-Sep-03

ATTENTION: Bob Carmichael

No. of samples received: 78
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 19
Samples submitted by: Redfern

ET #.	Tag #	SG g/cm^3
3	23751	2.73
5	23753	2.82
6	23754	3.16
7	23755	2.94
8	23756	2.75
9	23757	2.74
10	23758	2.92
11	23759	3.96
12	23760	4.02
13	23761	4.20
14	23762	3.80
15	23763	2.98
16	23764	3.84
17	23765	3.04
18	23766	3.61
20	23768	3.18
23	23771	3.11
24	23772	3.62
25	23773	3.76
26	23774	3.77
27	23775	3.78
28	23776	3.86
29	23777	4.05
30	23778	3.57
31	23779	3.85
32	23780	3.93
33	23781	3.47

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

ET #.	Tag #	SG g/cm^3
35	23783	3.97
36	23784	2.83
39	23787	3.20
42	23790	2.81
44	23792	2.94
47	23795	3.10
49	23797	3.19
50	23798	2.72
51	23799	2.54
76	23824	2.72

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

15-Sep-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-365

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 78
Sample type: Rock
Project #: Tulsequah Chief
Shipment #: 19
Samples submitted by: Redfern

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	23749	12.2	1.54	15	105	<5	0.31	12	6	47	395	1.66	<10	1.19	353	1	0.07	5	190	844	<5	<20	28	0.07	<10	<1	<10	3	2766
2	23750	8.1	1.30	15	60	<5	0.22	10	5	40	224	1.70	<10	1.02	318	3	0.06	4	230	1022	<5	<20	20	0.06	<10	<1	<10	3	2471
3	23751	>30	0.92	25	25	<5	0.29	55	5	53	1806	1.62	<10	0.65	178	<1	0.04	1	190	5824	25	<20	38	0.03	<10	<1	<10	2	>10000
4	23752	>30	1.41	550	10	<5	0.20	43	6	27	6497	3.41	<10	1.62	201	<1	0.04	6	490	4208	235	<20	16	<0.01	<10	2	<10	2	>10000
5	23753	>30	0.77	30	20	<5	0.53	118	5	56	2915	3.80	<10	0.53	100	<1	0.04	<1	220	7932	50	<20	34	0.01	<10	<1	<10	2	>10000
6	23754	>30	0.58	120	5	<5	0.51	177	5	53	4363	4.66	<10	0.48	68	<1	0.02	<1	230	5460	125	<20	19	<0.01	<10	<1	<10	2	>10000
7	23755	>30	0.69	230	20	<5	0.38	301	7	68	4404	5.56	<10	0.53	111	<1	0.02	<1	280	>10000	255	<20	18	0.01	<10	<1	<10	1	>10000
8	23756	>30	1.02	115	55	<5	0.64	75	3	101	>10000	2.57	<10	0.45	109	<1	0.05	<1	600	1106	110	<20	41	0.02	<10	<1	<10	<1	>10000
9	23757	>30	0.62	45	15	<5	0.46	80	5	48	7913	4.06	<10	0.49	55	<1	0.03	<1	370	2574	30	<20	21	0.01	<10	<1	<10	2	>10000
10	23758	24.1	0.34	60	<5	<5	0.25	77	7	67	2042	7.87	10	0.30	<1	<1	0.01	<1	260	5160	25	<20	11	<0.01	<10	<1	<10	2	>10000
11	23759	>30	0.07	1155	5	<5	0.11	>1000	3	23	>10000	3.12	<10	0.05	18	<1	<0.01	<1	330	>10000	895	<20	26	<0.01	<10	<1	<10	<1	>10000
12	23760	>30	0.01	3145	<5	<5	<0.01	799	1	<1	>10000	3.49	<10	0.04	<1	<1	<0.01	<1	510	>10000	425	<20	23	<0.01	<10	<1	<10	<1	>10000
13	23761	>30	0.01	3225	<5	<5	<0.01	847	<1	13	>10000	2.12	<10	0.02	34	<1	<0.01	<1	610	>10000	710	<20	24	<0.01	<10	<1	<10	<1	>10000
14	23762	>30	0.05	2035	<5	<5	0.03	997	<1	12	>10000	2.06	<10	0.04	72	<1	<0.01	<1	210	>10000	700	<20	28	<0.01	<10	<1	<10	<1	>10000
15	23763	>30	0.31	465	<5	<5	0.15	125	6	50	6443	5.74	<10	0.24	<1	<1	<0.01	<1	310	6898	190	<20	11	<0.01	<10	<1	<10	2	>10000
16	23764	>30	0.03	2755	10	<5	0.04	940	4	25	>10000	4.04	<10	0.06	52	<1	<0.01	<1	390	>10000	200	<20	35	<0.01	<10	<1	<10	2	>10000
17	23765	>30	1.28	770	30	<5	0.16	162	5	47	>10000	5.80	<10	1.65	271	<1	0.02	<1	640	3516	130	<20	15	0.01	<10	<1	<10	2	>10000
18	23766	>30	0.63	615	65	<5	0.20	117	11	103	>10000	>10	40	1.18	11	<1	0.03	<1	>10000	388	105	<20	20	<0.01	<10	<1	<10	1	>10000
19	23767	<0.2	1.81	<5	120	<5	1.40	<1	38	82	85	3.33	10	1.15	333	4	0.19	27	910	26	<5	<20	90	0.12	<10	38	<10	7	42
20	23768	>30	1.04	1835	35	<5	0.13	251	8	64	>10000	>10	20	1.59	212	<1	0.01	<1	>10000	236	365	<20	14	<0.01	<10	<1	<10	<1	>10000
21	23769	17.6	1.55	80	15	<5	0.07	2	9	86	6647	>10	30	2.52	89	<1	0.01	5	200	56	<5	<20	5	<0.01	<10	<1	<10	2	1204
22	23770	16.9	1.64	80	15	<5	0.08	4	9	93	7418	>10	30	2.61	97	<1	0.01	8	220	52	<5	<20	6	<0.01	<10	<1	<10	2	1433
23	23771	>30	1.31	600	35	<5	0.19	8	8	57	>10000	9.81	20	1.86	97	<1	0.01	4	690	316	100	<20	10	0.01	<10	<1	<10	2	1949
24	23772	>30	0.44	3615	50	<5	0.20	284	9	55	>10000	>10	20	0.68	313	<1	<0.01	<1	>10000	>10000	680	<20	26	<0.01	<10	<1	<10	<1	>10000
25	23773	>30	0.83	320	25	<5	0.13	10	10	87	>10000	>10	30	1.39	<1	<1	<0.01	2	620	664	40	<20	8	0.01	<10	<1	<10	2	2949

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	23774	>30	0.22	1150	<5	<5	0.12	174	9	105	>10000	>10	30	0.26	<1	<1	<0.01	<1	740	6996	165	<20	9	<0.01	<10	<1	<10	3	>10000
27	23775	>30	0.14	1065	<5	<5	0.08	155	8	113	>10000	>10	30	0.22	<1	<1	<0.01	<1	690	4364	325	<20	9	<0.01	<10	<1	<10	2	>10000
28	23776	>30	0.28	520	20	<5	0.12	127	10	116	>10000	>10	30	0.41	<1	<1	<0.01	<1	800	>10000	195	<20	8	0.01	<10	<1	<10	4	>10000
29	23777	>30	0.27	460	20	<5	0.13	112	9	104	>10000	>10	20	0.40	<1	<1	<0.01	<1	860	>10000	175	<20	10	0.01	<10	<1	<10	3	>10000
30	23778	>30	0.50	35	20	<5	0.21	<1	11	109	>10000	>10	30	0.48	<1	<1	0.01	25	520	112	<5	<20	5	<0.01	<10	1	<10	3	880
31	23779	18.4	0.11	45	<5	<5	0.07	2	8	95	>10000	>10	20	0.24	<1	<1	<0.01	2	560	216	<5	<20	7	<0.01	<10	<1	<10	3	1047
32	23780	>30	0.09	145	<5	<5	0.04	4	8	125	>10000	>10	30	0.20	<1	<1	<0.01	<1	710	176	5	<20	9	<0.01	<10	<1	<10	3	1153
33	23781	19.9	0.12	265	<5	<5	0.09	27	8	100	>10000	>10	30	0.23	<1	<1	<0.01	<1	>10000	1264	20	<20	4	<0.01	<10	<1	<10	2	6784
34	23782	22.1	0.12	195	<5	<5	0.08	<1	8	91	8580	>10	30	0.20	<1	<1	<0.01	<1	310	122	20	<20	3	<0.01	<10	<1	<10	2	673
35	23783	>30	0.07	135	<5	<5	0.05	7	8	83	>10000	>10	20	0.20	<1	<1	<0.01	5	570	260	10	<20	10	<0.01	<10	<1	<10	2	1975
36	23784	27.9	0.37	665	10	<5	0.41	47	7	80	6889	6.74	10	0.18	<1	<1	0.01	<1	380	3454	75	<20	16	<0.01	<10	<1	<10	3	>10000
37	23785	8.6	0.45	160	15	<5	0.38	<1	11	97	2947	5.23	<10	0.08	<1	2	0.02	8	430	168	20	<20	8	<0.01	<10	1	<10	2	424
38	23786	7.9	0.41	85	30	<5	0.25	4	9	90	3194	2.79	<10	0.05	<1	3	0.01	7	320	664	20	<20	6	<0.01	<10	2	<10	2	1265
39	23787	>30	0.18	730	<5	<5	0.12	289	10	104	>10000	>10	20	0.16	<1	<1	<0.01	<1	640	>10000	480	<20	13	<0.01	<10	<1	<10	4	>10000
40	23788	29.9	0.09	280	<5	<5	0.04	34	7	98	3310	>10	20	0.17	<1	<1	<0.01	<1	160	2102	70	<20	13	<0.01	<10	<1	<10	3	7935
41	23789	15.7	0.26	135	15	<5	0.18	34	7	196	1387	2.07	<10	0.06	50	6	<0.01	7	100	238	40	<20	14	<0.01	<10	3	<10	<1	8102
42	23790	>30	0.29	160	<5	<5	0.14	54	8	147	2631	7.30	10	0.16	<1	<1	<0.01	4	140	2438	75	<20	15	<0.01	<10	3	<10	2	>10000
43	23791	>30	1.49	580	15	<5	0.20	42	6	28	6306	3.55	<10	1.67	215	<1	0.04	7	570	4388	240	<20	17	<0.01	<10	3	<10	2	>10000
44	23792	>30	0.46	25	20	<5	0.29	123	9	126	6507	6.77	<10	0.30	<1	<1	0.01	12	350	3934	15	<20	28	<0.01	<10	6	<10	2	>10000
45	23793	16.1	5.54	85	45	<5	1.52	16	48	531	4188	6.72	10	6.01	839	<1	0.04	386	1750	558	<5	40	94	0.17	<10	130	<10	9	4230
46	23794	>30	0.11	1945	15	<5	0.14	748	3	21	>10000	3.05	<10	0.11	49	<1	<0.01	<1	640	>10000	980	<20	25	<0.01	<10	3	<10	<1	>10000
47	23795	>30	1.56	65	15	<5	1.10	231	23	227	>10000	>10	20	1.53	108	<1	0.01	101	1220	8098	35	<20	17	0.06	<10	22	<10	6	>10000
48	23796	15.5	0.33	40	15	<5	0.22	6	8	146	605	2.10	<10	0.17	43	5	<0.01	10	70	1306	20	<20	25	<0.01	<10	5	<10	2	1683
49	23797	29.9	0.49	40	10	<5	0.42	191	10	150	6752	>10	20	0.48	<1	<1	<0.01	8	370	7304	<5	<20	31	0.02	<10	<1	<10	5	>10000
50	23798	>30	0.27	70	<5	<5	0.20	65	9	95	2656	5.39	<10	0.21	<1	<1	<0.01	5	160	574	120	<20	35	<0.01	<10	5	<10	2	>10000
51	23799	>30	0.23	115	10	<5	0.12	48	5	111	796	2.93	<10	0.10	<1	4	<0.01	2	70	360	265	<20	28	<0.01	<10	4	<10	1	9735
52	23800	4.2	2.82	70	165	10	1.79	2	45	497	79	3.15	<10	3.42	371	<1	0.02	490	910	708	<5	40	174	0.08	<10	25	<10	4	579
53	23801	3.5	0.78	35	25	<5	0.35	8	4	106	155	3.25	<10	0.30	104	3	0.03	4	430	1454	20	<20	12	0.01	<10	<1	<10	5	2315
54	23802	0.8	1.18	30	50	<5	1.08	<1	9	81	54	3.34	<10	0.70	353	<1	0.08	11	730	72	<5	<20	41	0.06	<10	16	<10	7	231
55	23803	3.5	0.43	60	5	<5	0.22	15	4	89	182	3.96	<10	0.17	123	2	0.03	2	400	2042	20	<20	7	0.01	<10	<1	<10	6	4395
56	23804	2.2	0.55	45	45	<5	0.37	18	3	61	128	1.95	<10	0.22	243	<1	0.04	2	370	390	10	<20	2	0.03	<10	<1	<10	4	4699
57	23805	2.4	0.43	40	40	<5	0.36	4	3	58	78	1.95	<10	0.15	187	<1	0.04	2	350	704	10	<20	5	0.02	<10	<1	<10	3	1260
58	23806	2.7	0.57	20	95	<5	0.45	<1	2	68	36	1.26	<10	0.14	235	2	0.05	3	330	1156	90	<20	10	0.02	<10	<1	<10	3	253
59	23807	0.4	0.85	35	65	<5	0.47	<1	5	46	28	2.59	<10	0.36	588	<1	0.04	3	430	58	5	<20	6	0.05	<10	<1	<10	9	142
60	23808	3.8	1.28	140	45	<5	0.76	<1	11	94	55	3.62	<10	0.69	265	1	0.05	17	440	54	15	<20	37	0.07	<10	<1	<10	7	191
61	23809	4.9	1.13	275	35	<5	0.41	<1	8	71	24	4.59	<10	0.36	232	<1	0.04	6	320	22	10	<20	14	0.05	<10	<1	<10	5	66
62	23810	1.5	1.73	85	50	<5	0.49	<1	8	63	23	5.23	<10	0.86	417	1	0.02	8	420	28	5	<20	17	0.11	<10	<1	<10	8	83
63	23811	1.6	1.01	150	50	<5	0.39	<1	6	36	5	3.62	<10	0.38	334	<1	0.03	4	440	16	5	<20	5	0.07	<10	<1	<10	6	36
64	23812	0.2	1.83	<5	115	<5	1.67	<1	26	103	35	3.49	10	1.07	321	5	0.21	29	980	38	<5	<20	108	0.15	<10	33	<10	8	67
65	23813	3.5	0.81	430	30	<5	0.31	<1	5	43	11	3.77	<10	0.30	169	<1	0.05	4	400	18	10	<20	4	0.05	<10	<1	<10	5	41

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
66	23814	3.7	0.90	555	25	<5	0.42	<1	4	46	12	3.85	<10	0.30	118	<1	0.05	5	390	22	10	<20	3	0.04	<10	<1	<10	5	40
67	23815	4.8	0.48	180	25	<5	0.29	<1	2	92	28	2.40	<10	0.10	84	2	0.03	4	330	260	10	<20	8	<0.01	<10	<1	<10	4	725
68	23816	6.1	0.52	175	20	<5	0.30	6	3	79	64	3.16	<10	0.11	91	1	0.03	1	370	1166	30	<20	5	<0.01	<10	<1	<10	4	2809
69	23817	8.5	0.32	220	15	<5	0.25	14	3	78	152	3.86	<10	0.08	92	<1	0.01	<1	320	3508	60	<20	6	<0.01	<10	<1	<10	3	4565
70	23818	>30	0.11	2040	5	<5	0.14	835	3	22	>10000	4.03	<10	0.12	40	<1	0.02	<1	660	>10000	980	<20	22	<0.01	<10	3	<10	<1	>10000
71	23819	10.4	0.34	135	25	<5	0.28	18	9	60	134	3.82	<10	0.09	113	<1	0.01	<1	480	2986	40	<20	19	<0.01	<10	<1	<10	4	5538
72	23820	16.3	0.53	175	10	<5	0.48	6	20	71	115	5.95	<10	0.11	94	<1	0.01	4	1420	750	45	<20	21	<0.01	<10	2	<10	5	2512
73	23821	3.9	0.36	150	5	<5	0.63	4	9	55	75	5.28	<10	0.08	80	<1	0.01	2	2410	720	25	<20	25	<0.01	<10	<1	<10	6	1760
74	23822	2.8	0.47	180	20	<5	0.55	10	11	54	140	3.89	<10	0.10	195	<1	0.01	<1	1800	1586	45	<20	19	<0.01	<10	<1	<10	6	3292
75	23823	5.2	0.39	365	5	<5	0.35	35	8	98	2605	4.23	<10	0.10	169	<1	<0.01	1	850	1922	520	<20	35	<0.01	<10	<1	<10	4	9652
76	23824	4.8	0.34	340	<5	<5	0.32	46	7	84	2190	4.32	<10	0.09	169	<1	<0.01	<1	720	1982	550	<20	24	<0.01	<10	<1	<10	3	>10000
77	23825	7.5	0.60	195	15	<5	0.44	5	10	64	272	4.18	<10	0.21	170	2	0.01	10	490	432	80	<20	38	0.01	<10	<1	<10	3	2110
78	23826	2.8	0.52	165	40	<5	0.58	14	10	51	185	3.28	<10	0.16	133	<1	0.01	6	1450	1786	285	<20	37	<0.01	<10	<1	<10	5	4038
QC DATA:																													
Resplit:																													
1	23749	11.6	1.46	15	125	<5	0.28	11	6	48	320	1.65	<10	1.15	352	<1	0.07	5	200	778	<5	<20	23	0.07	<10	<1	<10	3	2628
36	23784	28.9	0.35	685	10	<5	0.39	44	9	85	5077	7.84	<10	0.17	<1	<1	<0.01	1	410	3588	70	<20	14	<0.01	<10	<1	<10	3	>10000
71	23819	10.6	0.34	135	25	<5	0.27	18	9	62	149	3.99	<10	0.08	110	<1	0.01	<1	490	2990	45	<20	18	<0.01	<10	<1	<10	4	5546
Repeat:																													
1	23749	12.6	1.51	15	110	<5	0.30	12	6	46	387	1.64	<10	1.17	348	<1	0.07	4	200	826	<5	<20	28	0.07	<10	<1	<10	3	2729
10	23758	24.2	0.34	65	<5	<5	0.25	72	6	65	1917	7.25	10	0.29	<1	<1	0.01	<1	260	4786	25	<20	13	<0.01	<10	<1	<10	2	>10000
19	23767	<0.2	1.81	<5	115	<5	1.42	<1	38	84	91	3.37	10	1.15	334	3	0.19	28	910	30	<5	<20	88	0.12	<10	32	<10	7	75
36	23784	28.1	0.39	695	10	<5	0.43	49	8	84	6384	7.47	10	0.19	<1	<1	0.01	<1	400	3538	90	<20	16	<0.01	<10	<1	<10	3	>10000
45	23793	16.0	5.56	95	50	<5	1.56	17	49	544	4130	6.88	10	6.03	856	<1	0.04	396	1790	578	<5	40	93	0.17	<10	136	<10	8	4405
54	23802	0.8	1.00	25	45	<5	0.90	<1	8	69	45	2.80	<10	0.57	298	<1	0.06	10	610	60	5	<20	35	0.05	<10	12	<10	6	185
71	23819	10.2	0.35	135	20	<5	0.28	18	9	63	132	3.87	<10	0.08	115	<1	0.01	1	520	3060	45	<20	18	<0.01	<10	<1	<10	4	5682
Standard:																													
GEO '03		1.6	1.59	65	140	<5	1.61	<1	19	59	99	3.58	10	0.95	627	<1	0.02	28	730	20	<5	<20	39	0.09	<10	68	<10	9	79
GEO '03		1.6	1.64	65	145	<5	1.78	<1	21	65	87	3.95	10	0.96	665	<1	0.03	33	810	24	<5	<20	38	0.10	<10	60	<10	10	83

JJ/kk
dl/365
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-368

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

19-Sep-03

ATTENTION: Bob Carmichael

No. of samples received: 46
Sample type: Core
Project #: Tulsequah
Shipment #: 21

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	23855	0.07	0.002					
2	23856	0.06	0.002					
3	23857	0.14	0.004					
4	23858	0.16	0.005					
5	23859	0.09	0.003					
6	23860	0.07	0.002					
7	23861	0.14	0.004					
8	23862	0.29	0.008					
9	23863	<0.03	<0.001					
10	23864	<0.03	<0.001					
11	23865	<0.03	<0.001					
12	23866	0.03	0.001					
13	23867	<0.03	<0.001					
14	23868	0.22	0.006					
15	23869	0.11	0.003					
16	23870	0.14	0.004					
17	23871	0.17	0.005					
18	23872	0.23	0.007					
19	23873	0.28	0.008					
20	23874	0.24	0.007	2.4	0.07	1.06	<0.01	0.01
21	23875	0.42	0.012					
22	23876	0.65	0.019					
23	23877	0.61	0.018					
24	23878	0.30	0.009					
25	23879	0.20	0.006					
26	23880	0.13	0.004					
27	23881	0.13	0.004					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. AK3-368 19-Sep-03

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
28	23882	0.09	0.003					
29	23883	0.05	0.001	1.4	0.04	0.17	<0.01	1.14
30	23884	0.08	0.002					
31	23885	0.28	0.008	22.0	0.64	0.21	0.65	6.97
32	23886	0.20	0.006					
33	23887	0.04	0.001					
34	23888	0.32	0.009					
35	23889	<0.03	<0.001					
36	23890	<0.03	<0.001					
37	23891	2.09	0.061	144	4.20	0.65	0.46	1.03
38	23892	0.04	0.001					
39	23893	0.03	0.001					
40	23894	2.06	0.060	326	9.51	1.56	10.1	14.8
41	23895	0.03	0.001					
42	23896	<0.03	<0.001					
43	23897	<0.03	<0.001					
44	23898	<0.03	<0.001					
45	23899	<0.03	<0.001					
46	23900	<0.03	<0.001					
QC DATA:								
Repeat:								
1	23855	0.06	0.002					
10	23864	<0.03	<0.001					
19	23873	0.27	0.008					
36	23890	<0.03	<0.001					
Standard:								
PM906		5.72	0.167					
PM906		5.64	0.164					
PB106				58.6	1.71	0.62	0.52	0.87

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

19-Sep-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-368

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: *Bob Carmichael*

No. of samples received: 46
Sample type: Core
Project #: Tulsequah
Shipment #:21

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	23855	<0.2	0.32	70	15	<5	0.40	4	7	51	90	2.73	<10	0.09	66	<1	0.01	1	1280	8	15	<20	15	0.01	<10	2	<10	5	1251
2	23856	0.3	0.38	65	45	<5	0.42	<1	9	50	147	2.05	<10	0.14	163	<1	0.01	2	1360	8	20	<20	5	0.03	<10	2	<10	6	255
3	23857	1.1	0.39	140	15	<5	0.43	<1	10	60	681	4.01	10	0.16	81	2	<0.01	2	1360	12	155	<20	13	0.02	<10	1	<10	6	156
4	23858	1.7	0.47	85	15	<5	0.41	<1	11	68	2683	5.02	10	0.24	109	<1	0.01	3	1270	10	20	<20	24	0.05	<10	1	<10	5	148
5	23859	0.7	0.57	75	15	<5	0.47	<1	11	56	885	4.11	10	0.26	149	2	0.02	4	1320	10	20	<20	10	0.04	<10	<1	<10	5	62
6	23860	0.4	0.61	75	20	<5	0.43	<1	12	60	329	4.21	10	0.33	218	<1	0.02	2	1300	8	15	<20	7	0.07	<10	1	<10	5	64
7	23861	1.3	0.32	100	10	<5	0.35	<1	9	55	2825	4.77	10	0.18	77	1	<0.01	1	1310	6	15	<20	3	0.04	<10	2	<10	4	226
8	23862	1.3	0.30	140	10	<5	0.38	2	7	64	1325	3.96	10	0.12	50	<1	<0.01	2	1320	8	45	<20	6	0.02	<10	2	<10	4	562
9	23863	<0.2	2.16	<5	330	<5	0.52	<1	5	61	5	1.43	10	1.78	226	2	0.09	7	220	18	<5	<20	54	0.01	<10	4	<10	5	143
10	23864	<0.2	2.48	5	490	<5	0.84	<1	5	56	211	1.72	<10	1.62	264	<1	0.15	8	330	20	<5	<20	68	0.03	<10	3	<10	5	154
11	23865	<0.2	2.63	5	615	<5	0.32	<1	5	62	40	1.84	<10	1.91	221	2	0.10	9	250	20	<5	<20	52	0.05	<10	5	<10	3	186
12	23866	<0.2	2.49	10	250	<5	0.30	<1	6	43	68	1.79	<10	1.99	243	<1	0.08	8	240	28	<5	<20	33	0.03	<10	6	<10	2	375
13	23867	<0.2	1.84	<5	170	<5	1.29	<1	23	88	47	3.25	10	1.02	271	10	0.23	28	840	28	<5	<20	97	0.43	<10	52	<10	9	51
14	23868	4.2	0.99	100	40	<5	1.70	33	10	85	2450	6.19	20	0.48	93	2	0.06	8	90	860	<5	<20	38	0.02	<10	3	<10	2	7362
15	23869	1.4	0.18	200	10	<5	0.25	<1	5	74	855	4.53	10	0.09	<1	2	0.02	7	20	82	15	<20	6	<0.01	<10	1	<10	<1	69
16	23870	2.9	0.20	235	<5	<5	0.23	<1	6	92	3191	5.64	10	0.11	<1	5	0.02	11	80	104	15	<20	10	0.02	<10	1	<10	<1	73
17	23871	1.6	0.19	380	10	<5	0.12	<1	9	78	615	5.02	<10	0.08	<1	15	0.02	30	<10	52	15	<20	3	<0.01	20	1	<10	<1	74
18	23872	2.4	0.21	530	5	<5	0.07	<1	16	121	888	5.04	<10	0.09	<1	23	0.02	72	20	108	15	<20	4	<0.01	30	2	<10	2	55
19	23873	3.8	0.25	1385	10	<5	0.12	<1	9	80	5506	4.49	<10	0.09	<1	4	0.03	24	150	38	35	<20	5	0.01	30	2	<10	3	80
20	23874	2.5	0.21	4375	10	<5	0.05	<1	7	59	>10000	4.74	10	0.10	8	8	0.02	5	210	8	70	<20	4	0.02	<10	<1	<10	<1	84
21	23875	2.2	0.20	1375	10	<5	0.04	<1	9	92	1916	>10	30	0.23	<1	<1	0.02	2	20	162	20	<20	4	<0.01	<10	<1	<10	<1	81
22	23876	6.0	0.15	1700	10	<5	0.04	6	8	115	720	>10	20	0.16	<1	5	0.01	<1	20	548	20	<20	2	<0.01	<10	1	<10	1	4110
23	23877	3.5	0.09	875	<5	<5	0.05	<1	9	94	491	>10	30	0.26	<1	<1	0.01	<1	<10	182	<5	<20	2	<0.01	<10	<1	<10	<1	1809
24	23878	1.5	0.20	455	<5	<5	0.04	<1	8	70	169	8.57	20	0.15	<1	7	0.02	4	<10	142	5	<20	4	<0.01	<10	<1	<10	<1	37
25	23879	1.1	0.20	315	5	<5	0.04	<1	6	70	769	6.63	10	0.12	<1	2	0.02	3	20	114	10	<20	3	<0.01	<10	<1	<10	<1	71

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	23880	0.9	0.31	515	10	<5	0.16	<1	6	82	2014	5.20	10	0.12	<1	4	0.03	1	50	88	25	<20	5	<0.01	<10	<1	<10	<1	117
27	23881	1.2	0.28	825	15	<5	0.11	<1	6	84	3390	5.08	20	0.10	<1	3	0.03	2	90	50	30	<20	6	<0.01	<10	1	<10	<1	136
28	23882	0.7	0.26	1010	10	<5	0.11	<1	6	83	5229	3.77	<10	0.09	<1	5	0.03	2	150	20	45	<20	6	0.01	<10	<1	<10	<1	273
29	23883	1.1	0.23	415	15	<5	0.08	47	5	68	1618	2.58	<10	0.08	17	<1	0.02	<1	50	12	20	<20	6	<0.01	<10	<1	<10	<1	>10000
30	23884	1.0	0.97	50	20	<5	0.62	37	8	78	640	2.65	<10	0.32	69	1	0.10	12	270	44	<5	<20	33	0.01	<10	8	<10	1	8928
31	23885	21.3	1.37	520	25	<5	1.69	278	6	45	2020	3.51	10	0.34	103	<1	0.14	<1	320	6858	45	<20	75	<0.01	<10	2	<10	<1	>10000
32	23886	5.0	0.82	100	25	<5	0.76	6	8	46	87	3.38	10	0.21	23	1	0.09	4	130	2118	10	<20	40	<0.01	<10	2	<10	1	5558
33	23887	0.9	1.30	35	30	<5	0.15	<1	7	55	32	1.92	<10	0.70	93	<1	0.06	6	90	12	<5	<20	14	0.02	<10	4	<10	2	96
34	23888	5.8	0.95	140	5	<5	0.53	<1	10	61	34	5.19	10	0.46	11	5	0.08	4	40	892	<5	<20	39	<0.01	<10	3	<10	2	2757
35	23889	0.5	1.11	35	30	<5	0.16	<1	6	56	23	1.95	<10	0.55	89	1	0.05	4	160	8	<5	<20	12	<0.01	<10	4	<10	2	61
36	23890	0.2	0.94	40	50	<5	0.23	<1	7	60	23	1.83	<10	0.33	67	3	0.07	4	150	10	<5	<20	19	<0.01	<10	3	<10	2	28
37	23891	>30	1.45	605	15	<5	0.21	50	7	27	6613	3.60	10	1.66	212	<1	0.04	9	420	4666	260	<20	19	0.05	<10	4	<10	2	>10000
38	23892	<0.2	0.81	30	70	<5	0.20	<1	6	62	20	1.46	<10	0.31	74	3	0.06	3	150	8	<5	<20	17	<0.01	<10	2	<10	2	27
39	23893	0.2	1.00	35	70	<5	0.45	<1	8	48	37	1.60	<10	0.29	73	1	0.07	5	140	10	<5	<20	34	<0.01	<10	2	<10	2	30
40	23894	>30	0.11	1730	<5	<5	0.12	863	5	22	>10000	3.75	<10	0.13	39	<1	<0.01	<1	320	>10000	950	<20	20	0.06	<10	4	<10	<1	>10000
41	23895	0.4	1.32	20	90	<5	0.52	<1	8	58	56	1.78	<10	0.59	159	3	0.13	6	140	30	<5	<20	24	0.03	<10	3	<10	3	137
42	23896	<0.2	1.28	15	75	<5	0.52	<1	8	49	19	1.87	<10	0.63	209	2	0.12	7	140	10	<5	<20	17	0.03	<10	2	<10	4	66
43	23897	<0.2	1.37	10	70	<5	0.42	<1	6	64	16	1.78	<10	0.70	235	3	0.10	5	130	10	<5	<20	15	0.02	<10	3	<10	3	59
44	23898	0.2	1.32	10	80	<5	0.42	<1	8	50	14	2.02	<10	0.77	285	1	0.09	6	140	12	<5	<20	11	0.02	<10	3	<10	3	77
45	23899	<0.2	1.17	15	90	<5	0.14	<1	7	57	9	2.00	<10	0.73	204	4	0.06	4	110	8	<5	<20	7	0.03	<10	<1	<10	1	76
46	23900	<0.2	1.19	40	30	<5	0.06	<1	8	65	10	3.99	<10	0.82	173	6	0.04	6	70	8	<5	<20	4	0.04	<10	<1	<10	2	78
QC DATA:																													
Resplit:																													
1	23855	<0.2	0.33	70	10	<5	0.41	4	8	71	77	2.90	<10	0.10	73	2	0.01	1	1310	8	15	<20	12	0.02	<10	2	10	4	1228
36	23890	0.3	0.96	45	60	<5	0.26	<1	7	60	21	1.81	<10	0.32	72	2	0.07	5	150	10	5	<20	19	<0.01	<10	3	<10	2	28
Repeat:																													
1	23855	<0.2	0.32	65	10	<5	0.40	5	8	52	87	2.77	<10	0.09	67	<1	<0.01	4	1300	8	15	<20	13	0.01	<10	2	<10	5	1311
10	23864	<0.2	2.44	5	500	<5	0.84	<1	5	57	208	1.71	<10	1.59	264	<1	0.14	9	330	20	5	<20	68	0.05	<10	3	<10	5	150
19	23873	3.9	0.25	1880	15	<5	0.12	2	12	84	7114	5.79	20	0.11	<1	3	0.02	32	150	40	45	<20	4	0.01	30	2	<10	2	108
36	23890	<0.2	0.98	45	55	<5	0.24	<1	7	61	22	1.88	<10	0.34	71	3	0.07	5	160	10	<5	<20	19	<0.01	<10	3	<10	2	30
45	23899	<0.2	1.20	20	95	<5	0.15	<1	7	58	9	2.03	<10	0.73	208	4	0.06	4	110	8	<5	<20	8	0.03	<10	<1	<10	2	78
Standard:																													
GEO '03		1.5	1.61	70	140	<5	1.61	<1	19	59	87	3.58	10	0.94	617	<1	0.03	30	650	22	<5	<20	41	0.11	<10	61	<10	9	76
GEO '03		1.5	1.59	60	140	<5	1.59	<1	21	60	88	3.62	10	0.94	630	6	0.02	32	670	22	<5	<20	39	0.11	<10	56	<10	9	79

JJ/kk
df/368
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-375

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

23-Sep-03

ATTENTION: Bob Carmichael

No. of samples received: 50
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 22

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	23901	<0.03	<0.001					
2	23902	<0.03	<0.001					
3	23903	<0.03	<0.001					
4	23904	<0.03	<0.001					
5	23905	<0.03	<0.001					
6	23906	<0.03	<0.001					
7	23907	0.03	0.001					
8	23908	0.33	0.010					
9	23909	0.19	0.006					
10	23910	0.22	0.006					
11	23911	0.04	0.001					
12	23912	<0.03	<0.001					
13	23913	0.05	0.001					
14	23914	0.31	0.009	1.6	0.05	0.11	0.05	1.07
15	23915	0.08	0.002					
16	23916	0.03	0.001					
17	23917	0.09	0.003					
18	23918	2.06	0.060	318	9.27	1.47	9.93	14.3
19	23919	0.12	0.003					
20	23920	0.07	0.002					
21	23921	0.11	0.003					
22	23922	0.11	0.003					
23	23923	0.25	0.007	4.9	0.14	0.06	0.01	1.30
24	23924	0.30	0.009	5.4	0.16	0.09	0.01	1.32
25	23925	0.12	0.003	1.8	0.05	0.07	0.03	0.66
26	23926	0.10	0.003					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. AK3-375 23-Sep-03

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
27	23927	0.04	0.001					
28	23928	0.05	0.001					
29	23929	0.05	0.001					
30	23930	0.03	0.001					
31	23931	<0.03	<0.001					
32	23932	0.04	0.001					
33	23933	0.04	0.001					
34	23934	0.10	0.003					
35	23935	0.13	0.004					
36	23936	0.10	0.003					
37	23937	0.04	0.001					
38	23938	0.05	0.001					
39	23939	0.04	0.001					
40	23940	0.03	0.001					
41	23941	<0.03	<0.001					
42	23942	<0.03	<0.001					
43	23943	0.06	0.002					
44	23944	0.11	0.003					
45	23945	0.07	0.002					
46	23946	0.07	0.002					
47	23947	<0.03	<0.001					
48	23948	0.03	0.001					
49	23949	0.03	0.001					
50	23950	<0.03	<0.001					
QC DATA:								
Resplit:								
1	23901	<0.03	<0.001					
36	23936	0.11	0.003					
Repeat:								
1	23901	<0.03	<0.001					
10	23910	0.25	0.007					
19	23919	0.11	0.003					
36	23936	0.10	0.003					
Standard:								
PG102		0.06	0.002					
PG102		0.06	0.002					
Pb106				58.6	1.71	0.62	0.53	0.85

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
XLS/03

19-Sep-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-375

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: **Bob Carmichael**

No. of samples received: 50
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 22

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	23901	<0.2	1.43	15	55	<5	0.07	<1	10	60	8	2.84	10	1.00	285	3	0.04	5	90	24	5	<20	4	0.05	<10	<1	<10	2	104
2	23902	0.2	1.72	10	55	<5	0.12	<1	11	68	9	2.77	10	1.24	327	1	0.05	5	110	26	<5	<20	4	0.05	<10	<1	<10	2	91
3	23903	0.3	2.44	10	60	<5	0.14	<1	12	83	11	2.86	20	2.15	446	1	0.06	8	140	48	<5	<20	5	0.09	<10	<1	<10	3	104
4	23904	0.4	1.92	10	65	<5	0.17	<1	11	60	13	2.39	10	1.59	316	2	0.05	7	90	30	<5	<20	7	0.05	<10	<1	<10	2	78
5	23905	0.2	2.29	10	90	<5	0.18	<1	6	77	8	1.61	<10	2.06	549	2	0.05	9	140	34	<5	<20	6	0.06	<10	<1	<10	2	110
6	23906	0.2	1.57	10	60	<5	0.18	<1	4	70	13	1.87	<10	1.30	390	2	0.04	6	120	26	<5	<20	5	0.02	<10	<1	<10	1	96
7	23907	1.0	0.32	75	30	<5	0.18	<1	8	34	102	3.56	<10	0.09	6	2	0.02	29	470	86	5	<20	1	<0.01	<10	1	<10	4	59
8	23908	7.1	0.24	815	10	<5	0.10	<1	26	75	1573	>10	40	0.22	<1	<1	0.01	16	240	246	40	<20	2	<0.01	<10	4	<10	4	372
9	23909	4.7	0.31	485	20	<5	0.18	17	38	91	1301	>10	40	0.22	<1	<1	0.02	5	400	5168	25	<20	2	<0.01	<10	10	<10	3	5303
10	23910	6.5	0.34	660	50	<5	0.19	13	40	84	2819	>10	70	0.24	<1	<1	0.02	6	380	588	35	<20	5	<0.01	<10	11	<10	<1	2026
11	23911	0.8	0.37	90	40	<5	0.20	<1	44	65	304	9.97	40	0.14	<1	<1	0.02	10	560	120	<5	<20	1	<0.01	<10	12	<10	2	497
12	23912	<0.2	1.85	<5	190	<5	1.71	<1	20	107	25	3.66	20	1.02	315	10	0.23	31	940	44	<5	<20	93	0.49	<10	33	<10	14	60
13	23913	0.4	0.40	55	20	<5	0.21	4	42	58	141	7.98	20	0.12	<1	<1	0.02	10	540	132	<5	<20	2	<0.01	<10	14	<10	3	1518
14	23914	1.9	0.38	50	20	<5	0.23	48	56	97	965	>10	40	0.28	<1	<1	0.03	12	140	504	<5	<20	4	<0.01	<10	13	<10	1	>10000
15	23915	0.8	0.47	45	25	<5	0.26	3	58	40	203	7.59	20	0.15	<1	<1	0.04	17	490	274	<5	<20	5	<0.01	<10	14	<10	2	1049
16	23916	0.6	0.56	20	25	<5	0.29	<1	33	56	89	6.74	20	0.16	<1	<1	0.05	12	290	212	<5	<20	6	<0.01	<10	14	<10	2	657
17	23917	1.2	0.45	35	30	<5	0.21	<1	45	58	116	9.02	30	0.16	<1	<1	0.03	18	130	118	<5	<20	6	<0.01	<10	13	<10	<1	317
18	23918	>30	0.12	1550	25	<5	0.13	847	6	25	>10000	4.59	20	0.14	34	<1	<0.01	<1	330	>10000	1015	<20	14	<0.01	<10	4	<10	<1	>10000
19	23919	1.6	0.45	45	20	<5	0.23	3	50	43	120	7.00	20	0.13	<1	<1	0.04	24	150	134	<5	<20	7	<0.01	<10	11	<10	1	1019
20	23920	0.9	0.41	45	15	<5	0.24	<1	47	39	105	7.18	20	0.13	<1	<1	0.03	23	550	76	<5	<20	3	<0.01	<10	13	<10	2	111
21	23921	3.2	1.11	80	30	<5	0.50	3	44	72	788	>10	20	0.51	133	<1	0.07	23	420	120	<5	<20	12	0.02	<10	24	<10	3	1023
22	23922	2.0	2.81	60	50	<5	0.76	3	55	76	421	>10	30	2.30	1196	<1	0.07	23	770	72	<5	<20	8	0.07	<10	84	<10	3	1621
23	23923	4.6	1.81	120	40	<5	0.70	64	45	64	643	9.24	30	1.13	763	<1	0.06	14	480	130	<5	<20	7	0.04	<10	48	<10	2	>10000
24	23924	5.3	1.81	115	55	<5	0.65	65	47	69	915	9.38	40	1.25	778	<1	0.06	15	440	112	5	<20	7	0.03	<10	51	<10	2	>10000
25	23925	2.1	1.39	210	10	<5	0.74	30	41	66	730	8.15	10	0.64	540	<1	0.07	14	558	261	<5	<20	9	0.03	<10	30	<10	4	6356

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY-AK3-382

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

22-Sep-03

ATTENTION: **Bob Carmichael**

ET #.	Tag #	SG g/cm^3
10	23960	2.80
11	23961	3.10
13	23963	2.74
16	23966	2.63

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-382

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

19-Sep-03

ATTENTION: Bob Carmichael

No. of samples received: 50
Sample type: Rock Core
Project #: Tulsequah Chief
Shipment #: 23
Samples Submitted by: Redfern

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	23951	0.04	0.001					
2	23952 Std B	2.06	0.060	142	4.14	0.66	0.48	1.02
3	23953	0.04	0.001					
4	23954	0.03	0.001					
5	23955	0.03	0.001					
6	23956	<0.03	<0.001					
7	23957	<0.03	<0.001					
8	23958	<0.03	<0.001					
9	23959	0.06	0.002					
10	23960	4.21	0.123	58.9	1.72	0.02	0.60	1.01
11	23961	4.67	0.136	216	6.30	0.08	1.14	2.09
12	23962	0.13	0.004					
13	23963	8.46	0.247	464	13.53	0.09	0.45	0.71
14	23964	0.49	0.014					
15	23965	0.25	0.007					
16	23966	1.93	0.056	44.4	1.30	0.01	0.01	0.03
17	23967	<0.03	<0.001					
18	23968	0.11	0.003					
19	23969	0.12	0.003					
20	23970	0.13	0.004					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
21	23971	0.56	0.016					
22	23972	0.26	0.008					
23	23973	0.17	0.005					
24	23974	0.11	0.003					
25	23975	0.03	0.001					
26	23976	0.21	0.006					
27	23977	0.15	0.004					
28	23978	0.09	0.003					
29	23979	0.20	0.006					
30	23980	0.28	0.008					
31	23981	0.40	0.012					
32	23982	0.30	0.009					
33	23983	0.13	0.004					
34	23984	0.08	0.002					
35	23985	0.06	0.002					
36	23986	0.03	0.001					
37	23987	0.10	0.003					
38	23988	0.09	0.003					
39	23989	0.52	0.015					
40	23990	0.08	0.002					
41	23991 Std B	2.09	0.061	140	4.08	0.66	0.48	1.02
42	23992	0.57	0.017					
43	23993	0.18	0.005					
44	23994 Std B	2.12	0.062	306	8.92	1.49	9.97	14.10
45	23995	0.18	0.005					
46	23996	0.04	0.001					
47	23997	0.07	0.002					
48	23998	0.05	0.001					
49	23999	0.07	0.002					
50	24000	0.04	0.001					

QC DATA:

Resplit:

1	23951	0.34	0.010
36	23986	0.03	0.001

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. AK3-382 19-Sep-03

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
QC DATA:								
Repeat:								
1	23951	0.03	0.001					
10	23960	4.17	0.122					
11	23961	4.91	0.143					
13	23963	7.84	0.229					
13	23963	8.53	0.249					
16	23966	1.87	0.055					
19	23969	0.19	0.006					
36	23986	0.03	0.001					
Standard:								
PM906		5.10	0.149					
PM906		5.63	0.164					
Pb106				58.8	1.72	0.62	0.53	0.84

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

22-Sep-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-382

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 50
Sample type: Core
Shipment #:23

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	23951	0.3	0.30	30	5	<5	0.39	<1	5	68	52	4.29	<10	0.07	27	<1	0.01	2	190	8	<5	<20	8	<0.01	<10	<1	<10	4	123
2	23952 Std A	>30	1.48	520	20	<5	0.20	46	7	24	6315	3.40	<10	1.67	209	<1	0.04	9	280	4298	250	<20	14	0.03	<10	3	<10	3	9308
3	23953	0.7	0.32	70	5	<5	0.50	<1	7	64	101	6.17	<10	0.17	26	2	<0.01	2	520	12	10	<20	3	0.01	<10	<1	<10	7	112
4	23954	0.5	0.44	65	10	<5	0.76	<1	7	54	85	5.22	<10	0.15	53	2	<0.01	3	700	12	15	<20	2	0.01	<10	<1	<10	9	33
5	23955	0.5	0.42	105	<5	<5	0.74	<1	8	51	93	6.59	10	0.33	130	<1	<0.01	2	850	20	5	<20	<1	0.01	<10	<1	<10	10	57
6	23956	0.3	0.29	30	10	<5	0.36	<1	5	58	68	4.00	<10	0.18	86	<1	<0.01	2	560	12	10	<20	<1	<0.01	<10	<1	<10	6	43
7	23957	0.1	0.65	15	20	<5	0.47	<1	6	56	44	3.61	<10	0.27	243	<1	0.02	3	550	10	<5	<20	3	0.04	<10	<1	<10	5	107
8	23958	0.1	0.81	20	15	<5	0.57	<1	7	62	58	5.47	<10	0.32	215	<1	0.03	3	720	12	5	<20	4	0.03	<10	<1	<10	8	87
9	23959	1.9	3.16	20	45	5	2.16	<1	27	240	84	2.98	<10	2.52	466	3	0.28	111	1470	126	<5	60	134	0.11	<10	44	<10	6	238
10	23960	>30	0.21	115	5	<5	0.25	30	10	65	174	4.41	<10	0.08	<1	<1	0.02	2	40	5898	35	<20	15	<0.01	<10	1	<10	2	>10000
11	23961	>30	0.20	355	<5	<5	0.17	63	12	64	690	5.12	<10	0.11	<1	<1	0.02	2	30	>10000	115	<20	28	<0.01	<10	<1	<10	2	>10000
12	23962	3.8	0.68	60	35	<5	0.58	<1	10	45	41	3.07	<10	0.33	131	<1	0.05	5	100	104	10	<20	17	<0.01	<10	3	<10	3	346
13	23963	>30	0.29	300	40	<5	0.65	21	5	72	911	0.75	<10	0.12	42	<1	0.02	3	30	4326	540	20	38	<0.01	<10	<1	<10	1	7206
14	23964	6.1	1.18	50	40	<5	0.72	<1	11	62	78	2.29	<10	0.92	294	<1	0.08	10	150	130	20	<20	28	0.03	<10	23	<10	6	294
15	23965	19.7	1.96	95	50	<5	0.77	4	21	115	234	3.20	<10	1.76	445	1	0.13	27	270	742	80	<20	21	0.04	<10	76	<10	7	757
16	23966	>30	2.38	70	160	<5	0.68	<1	15	58	86	2.57	<10	2.09	563	3	0.12	20	210	98	35	<20	23	0.06	<10	65	<10	5	265
17	23967	0.2	2.07	5	200	5	1.44	<1	19	86	26	3.26	10	1.07	287	4	0.27	29	560	34	5	<20	139	0.19	<10	26	<10	10	51
18	23968	1.8	3.30	20	105	<5	1.90	3	13	103	270	2.47	<10	1.24	423	<1	0.27	31	330	108	10	<20	191	0.07	<10	24	<10	6	662
19	23969	5.0	1.59	45	65	<5	1.05	12	8	73	357	2.08	<10	0.37	186	<1	0.19	10	230	812	10	<20	81	0.01	<10	4	<10	5	2621
20	23970	4.6	1.79	35	75	<5	1.17	12	8	68	395	2.00	<10	0.39	192	<1	0.21	11	240	820	10	<20	90	0.01	<10	6	<10	5	2723
21	23971	4.0	0.93	75	60	<5	0.76	11	5	93	293	1.90	<10	0.21	188	<1	0.12	8	180	632	5	20	37	0.01	<10	<1	<10	4	2596
22	23972	0.9	0.61	60	70	<5	0.44	<1	5	77	29	1.41	<10	0.13	145	<1	0.09	5	160	80	<5	<20	19	0.02	<10	<1	<10	5	121
23	23973	0.4	0.56	25	100	<5	0.41	<1	4	52	10	0.92	<10	0.10	117	<1	0.06	3	150	46	<5	<20	22	0.01	<10	<1	<10	3	92
24	23974	0.4	0.51	15	105	<5	0.27	<1	3	49	9	0.81	<10	0.11	114	<1	0.04	2	140	22	<5	<20	15	0.01	<10	<1	<10	4	47
25	23975	0.1	2.19	<5	475	<5	0.61	<1	4	46	14	1.37	<10	1.49	354	<1	0.13	7	160	22	5	<20	52	0.01	<10	1	<10	5	81

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	23976	3.6	0.57	100	20	<5	0.41	9	5	79	2230	3.13	<10	0.12	12	<1	0.06	3	100	58	25	<20	29	<0.01	<10	1	<10	3	1985
27	23977	2.1	0.28	160	15	<5	0.15	<1	6	78	1646	4.90	<10	0.09	<1	<1	0.03	1	70	64	30	<20	11	<0.01	<10	<1	<10	3	109
28	23978	1.2	0.23	85	10	<5	0.07	<1	7	85	51	4.60	<10	0.07	<1	<1	0.02	3	50	52	10	<20	6	<0.01	<10	1	<10	3	40
29	23979	3.3	0.21	185	<5	<5	0.07	<1	10	75	217	6.57	<10	0.09	<1	<1	0.02	2	120	20	5	<20	5	<0.01	<10	1	<10	4	28
30	23980	2.2	0.15	30	<5	<5	0.03	<1	10	84	184	>10	10	0.16	<1	<1	0.01	2	80	66	<5	<20	2	<0.01	<10	2	<10	5	876
31	23981	5.9	0.15	35	<5	<5	0.04	<1	13	89	1018	8.96	10	0.12	<1	<1	0.01	4	80	16	5	<20	2	<0.01	<10	2	<10	4	117
32	23982	2.4	0.26	160	<5	<5	0.12	<1	7	90	928	4.95	<10	0.13	<1	<1	0.02	3	130	18	10	<20	4	<0.01	<10	2	<10	3	118
33	23983	4.8	1.22	30	5	<5	0.15	<1	8	72	3382	8.71	10	1.38	35	<1	0.04	6	280	8	15	<20	6	0.02	<10	3	<10	5	150
34	23984	0.4	0.62	5	5	<5	0.16	<1	8	73	20	8.52	10	0.54	<1	<1	0.03	2	290	12	<5	<20	7	<0.01	<10	3	<10	5	22
35	23985	0.5	2.37	30	50	5	1.34	<1	27	91	65	4.32	10	2.00	495	4	0.25	28	1350	36	10	<20	69	0.04	<10	57	<10	11	163
36	23986	0.3	0.79	10	10	<5	0.15	<1	8	84	14	7.13	10	0.73	<1	<1	0.03	5	240	14	5	<20	8	<0.01	<10	3	<10	4	49
37	23987	1.1	0.84	10	20	<5	0.10	<1	8	81	42	5.74	<10	0.76	14	<1	0.03	4	80	44	<5	<20	6	<0.01	<10	3	<10	4	120
38	23988	0.9	1.53	50	15	10	0.93	<1	21	81	59	5.64	10	1.15	155	4	0.15	21	880	40	5	<20	44	0.03	<10	41	<10	9	130
39	23989	2.2	1.30	25	20	5	0.23	<1	9	93	43	6.03	<10	1.26	70	<1	0.06	8	120	38	5	<20	12	0.01	<10	3	<10	4	176
40	23990	2.0	1.50	20	40	<5	0.15	<1	8	74	40	2.62	<10	1.81	181	<1	0.04	8	80	38	<5	<20	12	<0.01	<10	2	<10	2	182
41	23991 Std A	>30	1.71	635	20	<5	0.25	57	8	32	6724	3.97	<10	1.91	246	<1	0.04	10	350	5390	305	<20	16	0.02	<10	3	<10	4	>10000
42	23992	1.9	1.89	35	20	<5	0.23	4	8	58	67	4.87	<10	2.31	184	<1	0.05	8	40	40	<5	<20	20	0.02	<10	2	<10	3	627
43	23993	0.6	1.14	20	25	<5	0.18	<1	7	57	15	3.65	<10	1.30	112	<1	0.03	6	120	46	5	<20	19	<0.01	<10	2	<10	3	121
44	*23994 Std A*	*>30*	*0.11*	*2280*	<5	<5	*0.13*	*871*	6	24	*>10000*	*4.76*	*<10*	*0.13*	*29*	*<1*	*<0.01*	*<1*	*260*	*>10000*	*1230*	*<20*	*14*	*0.02*	*<10*	3	*<10*	2	*>10000*
45	23995	0.3	1.41	20	15	<5	0.22	<1	5	64	11	2.79	<10	1.85	186	<1	0.02	8	80	26	<5	<20	19	<0.01	<10	2	<10	3	108
46	23996	1.8	1.12	25	15	<5	0.52	<1	6	73	28	2.58	<10	1.17	140	<1	0.04	7	100	18	<5	<20	55	<0.01	<10	1	<10	2	40
47	23997	2.4	1.22	30	10	<5	0.18	<1	10	68	203	4.74	<10	1.40	138	<1	0.03	6	110	20	<5	<20	14	<0.01	<10	1	<10	3	44
48	23998	1.3	1.38	40	10	<5	0.34	<1	9	76	620	5.30	<10	1.17	118	<1	0.07	7	120	16	5	<20	27	0.02	<10	<1	<10	4	55
49	23999	2.2	1.11	50	20	<5	0.58	<1	4	124	2144	2.21	<10	0.82	167	<1	0.06	7	90	28	5	20	60	0.02	<10	1	<10	2	86
50	24000	1.3	0.66	60	15	<5	0.15	<1	7	76	931	3.39	<10	0.58	66	<1	0.03	5	90	12	5	<20	11	<0.01	<10	1	<10	3	34
QC DATA:																													
Resplit:																													
1	23951	0.3	0.34	35	5	<5	0.41	<1	5	84	52	4.79	<10	0.07	32	<1	0.01	3	210	14	5	<20	6	<0.01	<10	<1	<10	4	125

Eco Tech Laboratory Ltd.

OCT 17 2003

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK3-393

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

2-Oct-03

ATTENTION: Bob Carmichael

ET #.	Tag #	SG g/cm^3
8	137958	3.21
25	137975	2.86
26	137976	3.37
28	137978	2.69
29	137979	2.74
31	137981	2.90
33	137983	2.90
43	137993	2.88
56	138056	2.73

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-393

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

30-Sep-03

ATTENTION: Bob Carmichael

No. of samples received: 65
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 24
Samples submitted by: S.C.

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	137951	0.04	0.001					
2	137952	<0.03	<0.001					
3	137953	<0.03	<0.001					
4	137954	0.04	0.001					
5	137955	<0.03	<0.001					
6	137956	0.04	0.001					
7	137957	0.07	0.002					
8	137958	0.48	0.014	12.3	0.36	0.62	0.83	19.0
9	137959	0.32	0.009					
10	137960	0.18	0.005					
11	137961	0.26	0.008					
12	137962	0.18	0.005					
13	137963	0.19	0.006					
14	137964	0.18	0.005					
15	137965	0.39	0.011					
16	137966	0.32	0.009					
17	137967	<0.03	<0.001					
18	137968	<0.03	<0.001					
19	137969	0.05	0.001					
20	137970	<0.03	<0.001					
21	137971	0.12	0.003					
22	137972	0.13	0.004					
23	137973	0.18	0.005					
24	137974	0.05	0.001					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. AK3-393 30-Sep-03

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
25	137975	0.20	0.006	4.4	0.13	0.25	0.02	1.63
26	137976	0.50	0.015	14.0	0.41	0.29	2.68	18.3
27	137977	<0.03	<0.001					
28	137978	2.95	0.086	46.7	1.36	0.03	0.26	1.01
29	137979	1.24	0.036	36.9	1.08	0.16	0.37	1.13
30	137980	0.55	0.016					
31	137981	3.13	0.091	80.6	2.35	0.35	0.67	3.09
32	137982	0.42	0.012					
33	137983	1.63	0.048	172	5.02	0.64	0.37	1.17
34	137984	0.34	0.010					
35	137985	<0.03	<0.001					
36	137986	0.14	0.004					
37	137987	0.16	0.005					
38	137988	0.09	0.003					
39	137989	0.05	0.001					
40	137990	0.18	0.005					
41	137991	2.18	0.064	139	4.05	0.65	0.47	1.03
42	137992	0.11	0.003					
43	137993	0.71	0.021	166	4.84	0.68	1.65	7.91
44	137994	2.15	0.063	314	9.16	1.50	10.6	14.8
45	137995	1.62	0.047					
46	137996	0.22	0.006					
47	137997	0.08	0.002					
48	137998	0.08	0.002					
49	138999	<0.03	<0.001					
50	137800	0.17	0.005					
51	138051	0.08	0.002					
52	138052	2.19	0.064	132	3.85	0.64	0.45	1.02
53	138053	<0.03	<0.001					
54	138054	<0.03	<0.001					
55	138055	<0.03	<0.001					
56	138056	0.12	0.003	36.7	1.07	0.08	0.13	0.25
57	138057	0.03	0.001					
58	138058	<0.03	<0.001					
59	138059	0.05	0.001					
60	138060	<0.03	<0.001					
61	138061	<0.03	<0.001					
62	138062	0.03	0.001					
63	138063	0.12	0.003					
64	138064	0.16	0.005					
65	138065	0.17	0.005					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. **AK3-393** 30-Sep-03

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
QC DATA:								
Repeat:								
1	137951	0.04	0.001					
6	137956	0.09	0.003					
8	137958	0.53	0.015					
9	137959	0.24	0.007					
23	137973	0.16	0.005					
25	137975	0.22	0.006					
27	137977	0.03	0.001					
29	137979	1.41	0.041					
31	137981	2.70	0.079					
33	137983	1.81	0.053					
36	137986	0.15	0.004					
38	137988	0.08	0.002					
50	137800	0.12	0.003					
56	138056	0.07	0.002					
64	138064	0.09	0.003					
Standard:								
PG102		0.07	0.002					
PB106				58.6	1.71	-	0.52	0.85

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

25-Sep-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-393

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 65
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 24
Samples submitted by: S.C.

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	137951	0.8	0.94	45	65	<5	0.28	<1	7	61	402	2.10	<10	0.63	130	<1	0.05	5	100	46	5	<20	18	<0.01	<10	1	<10	2	75
2	137952	0.2	1.99	<5	210	5	1.41	<1	15	90	45	3.50	10	1.03	311	4	0.23	31	950	68	5	<20	114	0.19	<10	25	<10	8	78
3	137953	1.5	1.33	40	50	<5	0.33	<1	7	61	433	3.22	<10	1.20	208	2	0.05	6	160	42	10	<20	20	<0.01	<10	2	<10	3	80
4	137954	1.7	0.73	10	30	<5	0.34	<1	5	93	21	3.10	<10	0.51	96	1	0.05	5	130	50	<5	<20	22	<0.01	<10	1	<10	3	81
5	137955	0.9	0.94	20	50	<5	0.39	<1	5	110	103	2.64	<10	0.62	115	5	0.05	7	160	44	10	<20	23	<0.01	<10	1	<10	3	79
6	137956	0.2	4.68	45	90	15	2.54	<1	37	138	58	5.70	10	2.91	342	4	0.56	71	2440	82	<5	<20	120	0.21	<10	77	<10	10	196
7	137957	1.2	1.24	100	50	<5	0.88	<1	6	70	522	2.88	<10	0.55	118	3	0.10	6	180	260	10	<20	67	<0.01	<10	<1	<10	5	352
8	137958	12.9	0.52	255	20	<5	0.51	710	10	44	5981	5.40	<10	0.23	13	<1	0.03	<1	320	8630	<5	<20	34	<0.01	<10	<1	<10	4	>10000
9	137959	2.1	3.31	35	95	<5	2.23	10	29	105	1293	4.81	10	1.88	412	3	0.34	54	2200	262	10	<20	96	0.19	<10	43	<10	10	2344
10	137960	2.6	0.30	100	<5	<5	0.23	21	10	90	519	9.01	20	0.16	<1	<1	0.02	3	150	738	20	<20	23	<0.01	<10	1	<10	5	5241
11	137961	4.3	2.51	405	80	<5	1.92	<1	34	176	1952	3.90	10	1.96	314	4	0.23	89	1680	68	60	<20	90	0.19	<10	15	<10	8	272
12	137962	1.7	2.77	55	90	<5	2.03	14	23	103	3164	4.60	10	1.71	397	3	0.29	53	2080	110	5	<20	79	0.18	<10	31	<10	9	3044
13	137963	3.6	0.37	415	10	<5	0.20	8	9	86	2285	9.19	20	0.14	<1	<1	0.03	2	210	32	50	<20	8	<0.01	<10	<1	<10	5	2014
14	137964	1.5	0.34	100	<5	<5	0.20	<1	9	113	2067	>10	20	0.20	<1	1	0.03	4	180	116	10	<20	7	<0.01	<10	<1	<10	5	766
15	137965	3.5	0.32	100	10	<5	0.16	3	7	96	1858	8.64	20	0.14	<1	2	0.03	2	150	176	5	<20	7	<0.01	<10	<1	<10	4	1136
16	137966	3.4	0.31	30	<5	5	0.12	4	10	128	116	>10	30	0.26	<1	1	0.02	3	120	148	10	<20	7	<0.01	<10	2	<10	5	1239
17	137967	0.2	2.05	5	190	10	1.46	<1	18	84	23	3.42	10	1.06	298	4	0.23	30	880	58	5	<20	169	0.19	<10	39	<10	9	63
18	137968	0.2	1.01	10	50	<5	0.19	<1	4	93	19	2.64	<10	0.96	222	4	0.03	7	210	28	<5	<20	10	<0.01	<10	3	<10	2	124
19	137969	0.2	0.52	20	35	<5	0.19	<1	5	64	12	3.03	<10	0.37	70	1	0.02	5	330	22	<5	<20	8	<0.01	<10	<1	<10	3	38
20	137970	0.2	0.58	25	40	<5	0.19	<1	5	86	14	3.07	<10	0.39	81	4	0.03	6	280	26	5	<20	8	<0.01	<10	1	<10	3	44
21	137971	2.5	0.40	160	15	5	0.22	<1	23	43	72	8.71	20	0.32	<1	<1	0.02	18	440	106	15	<20	10	<0.01	<10	7	<10	5	63
22	137972	0.9	2.11	90	10	<5	0.25	<1	33	80	87	>10	30	2.88	526	<1	0.01	18	100	66	<5	<20	5	<0.01	<10	58	<10	5	215
23	137973	1.4	0.39	130	<5	10	0.16	<1	18	100	160	>10	30	0.54	<1	<1	0.01	4	250	102	5	<20	4	<0.01	<10	10	<10	5	507
24	137974	2.1	0.31	225	5	<5	0.08	<1	37	57	5048	>10	20	0.23	<1	4	0.02	19	250	10	15	<20	7	<0.01	<10	12	<10	5	79
25	137975	4.6	0.71	25	10	<5	0.40	58	11	91	2434	6.39	10	0.39	1	<1	0.06	8	410	220	<5	<20	25	0.03	<10	3	<10	5	>10000

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	137976	13.7	0.18	465	10	<5	0.37	725	9	57	2630	7.20	10	0.11	<1	<1	0.01	<1	120	>10000	<5	<20	36	<0.01	<10	<1	<10	2	>10000
27	137977	1.3	1.61	<5	195	<5	0.96	<1	5	67	78	2.06	<10	0.86	283	<1	0.12	7	210	88	5	<20	90	0.04	<10	<1	<10	5	335
28	137978	>30	0.58	30	40	<5	0.56	46	8	69	369	2.59	<10	0.22	45	71	0.04	5	300	2418	40	<20	56	<0.01	<10	1	<10	5	>10000
29	137979	>30	0.64	45	20	<5	0.50	54	8	59	1602	4.20	<10	0.29	31	1	0.06	3	360	3420	65	<20	21	<0.01	<10	1	<10	5	>10000
30	137980	13.7	1.45	175	15	<5	1.07	3	19	117	446	>10	20	1.04	105	4	0.09	41	460	454	10	<20	37	0.04	<10	7	<10	7	1057
31	137981	>30	0.83	105	20	<5	0.95	162	8	74	3552	5.49	10	0.36	40	<1	0.07	<1	360	6430	175	<20	36	<0.01	<10	<1	<10	5	>10000
32	137982	21.9	2.65	35	25	<5	1.78	<1	12	80	2177	>10	30	1.97	191	9	0.13	10	420	690	10	<20	44	0.04	<10	<1	<10	7	1028
33	137983	>30	0.90	1040	30	<5	0.79	75	8	64	6563	5.65	10	0.35	<1	<1	0.08	4	520	3632	880	<20	36	<0.01	<10	2	<10	4	>10000
34	137984	12.6	0.61	60	10	<5	0.45	25	10	78	1308	9.06	20	0.29	<1	2	0.04	4	280	1386	20	<20	18	<0.01	<10	<1	<10	6	5918
35	137985	0.3	1.73	<5	225	5	0.97	<1	6	54	17	1.70	<10	0.99	303	<1	0.11	8	340	50	5	<20	71	0.03	<10	<1	<10	10	193
36	137986	0.9	2.21	5	95	<5	1.14	<1	12	91	17	2.58	<10	1.89	305	<1	0.08	38	490	54	10	<20	27	0.03	<10	18	<10	8	92
37	137987	12.8	0.54	15	15	<5	0.46	43	8	96	1385	3.15	<10	0.46	60	3	0.02	11	450	496	10	<20	9	<0.01	<10	4	<10	5	8743
38	137988	9.8	0.78	20	10	<5	0.62	33	12	93	3195	4.94	10	1.02	166	14	0.02	21	720	44	10	<20	16	<0.01	<10	9	<10	5	7442
39	137989	1.0	0.78	30	15	<5	0.60	<1	8	48	21	2.62	<10	1.14	208	3	<0.01	5	400	60	5	<20	9	<0.01	<10	2	<10	5	101
40	137990	0.4	0.21	15	30	<5	0.31	<1	5	76	47	1.54	<10	0.13	42	4	<0.01	3	310	42	5	<20	8	<0.01	<10	<1	<10	2	228
41	137991	>30	1.35	630	15	<5	0.22	54	8	29	6303	3.72	<10	1.55	204	<1	0.03	7	620	4258	305	<20	11	<0.01	<10	3	<10	4	>10000
42	137992	4.6	0.20	60	<5	<5	0.36	21	6	109	4250	4.01	<10	0.15	<1	4	<0.01	2	470	46	35	<20	3	<0.01	<10	<1	<10	4	4014
43	137993	>30	0.18	1805	<5	<5	0.75	347	7	49	6352	3.90	<10	0.21	29	<1	<0.01	<1	370	>10000	145	<20	24	<0.01	<10	<1	<10	4	>10000
44	137994	>30	0.11	1650	<5	<5	0.14	962	8	28	>10000	5.28	<10	0.11	26	<1	<0.01	<1	680	>10000	850	<20	10	<0.01	<10	2	<10	4	>10000
45	137995	14.4	0.17	180	35	<5	0.09	10	4	51	410	0.89	<10	0.04	4	2	<0.01	1	60	1050	65	<20	95	<0.01	<10	<1	<10	<1	2763
46	137996	8.2	0.90	255	15	<5	1.99	10	9	38	984	5.56	10	1.15	122	3	<0.01	8	290	400	150	<20	227	<0.01	<10	2	<10	4	2077
47	137997	1.2	3.24	20	5	10	3.46	<1	10	53	29	6.76	10	5.29	292	<1	<0.01	25	380	114	<5	<20	85	<0.01	<10	4	<10	4	154
48	137998	3.0	0.19	30	<5	10	0.21	<1	10	93	40	7.00	10	0.15	<1	4	<0.01	3	140	60	10	<20	1	<0.01	<10	<1	<10	3	151
49	138999	0.2	0.20	5	195	<5	1.06	<1	<1	70	4	0.37	10	0.02	608	2	0.03	5	50	56	<5	<20	31	<0.01	<10	<1	<10	6	85
50	137800	5.6	0.17	75	<5	10	0.18	<1	15	91	74	7.79	10	0.10	<1	4	<0.01	4	320	128	15	<20	<1	<0.01	<10	<1	<10	4	435
51	138051	1.5	0.17	<5	10	<5	0.62	<1	11	103	131	4.74	<10	0.08	56	1	<0.01	5	230	20	<5	<20	<1	<0.01	<10	<1	<10	4	156
52	138052	>30	1.39	720	15	<5	0.23	57	8	30	6292	3.88	<10	1.59	210	<1	0.04	8	800	4320	310	<20	10	<0.01	<10	3	<10	4	>10000
53	138053	1.2	0.42	<5	15	5	0.61	<1	10	136	33	3.87	<10	0.29	138	4	0.01	12	350	30	5	<20	7	<0.01	<10	4	<10	4	71
54	138054	0.7	0.18	<5	10	<5	0.28	<1	8	107	18	3.43	<10	0.09	55	<1	<0.01	4	200	8	<5	<20	6	<0.01	<10	1	<10	3	26
55	138055	0.8	0.15	<5	20	<5	0.23	<1	7	126	16	2.74	<10	0.07	44	4	<0.01	6	100	18	10	<20	4	<0.01	<10	<1	<10	2	25
56	138056	>30	0.13	15	<5	<5	0.63	12	12	123	879	5.00	<10	0.08	76	<1	<0.01	6	200	1214	50	<20	7	<0.01	<10	1	<10	3	2406
57	138057	2.1	0.19	<5	5	5	0.38	<1	11	113	25	4.61	<10	0.11	19	1	<0.01	7	130	52	<5	<20	10	<0.01	<10	1	<10	3	51
58	138058	0.2	2.41	10	110	15	2.87	<1	25	86	23	5.12	10	1.91	694	3	0.13	36	1950	48	10	<20	51	0.21	<10	48	<10	10	130
59	138059	0.3	0.22	<5	25	<5	0.34	<1	15	112	15	2.05	<10	0.10	59	13	<0.01	14	110	12	<5	<20	11	<0.01	<10	1	<10	2	39
60	138060	0.5	0.19	<5	20	<5	0.17	<1	12	90	511	2.26	<10	0.06	17	5	<0.01	8	170	10	5	<20	4	<0.01	<10	<1	<10	2	49

REDFERN RESOURCES LTD. ICP CERTIFICATE OF ANALYSIS AK 2003-393 ECO TECH LABORATORY LTD.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
61	138061	1.0	0.20	<5	10	10	0.27	<1	9	108	31	4.07	<10	0.11	34	6	<0.01	4	130	12	<5	<20	10	<0.01	<10	<1	<10	3	43
62	138062	1.9	0.23	<5	5	<5	0.53	<1	9	102	112	4.36	<10	0.15	114	4	<0.01	5	130	22	5	<20	41	<0.01	<10	<1	<10	3	43
63	138063	3.8	0.21	20	<5	<5	0.38	<1	8	117	1234	3.91	<10	0.12	50	10	<0.01	5	210	176	15	<20	23	<0.01	<10	<1	<10	3	183
64	138064	2.1	0.18	10	10	<5	0.37	<1	6	96	605	3.03	<10	0.09	40	5	<0.01	5	180	260	30	<20	9	<0.01	<10	<1	<10	3	396
65	138065	4.2	1.36	105	<5	5	0.94	<1	54	78	124	8.59	20	1.26	541	<1	0.01	29	830	70	<5	<20	43	0.04	<10	34	<10	8	495
QC DATA:																													
Resplit:																													
1	137951	1.0	0.89	40	40	<5	0.27	<1	7	61	376	2.12	<10	0.60	140	2	0.05	5	100	36	<5	<20	16	<0.01	<10	1	<10	3	70
36	137986	0.8	2.26	5	95	5	1.18	<1	12	97	17	2.61	<10	1.90	309	<1	0.08	39	540	60	<5	<20	32	0.03	<10	14	<10	8	103
Repeat:																													
1	137951	0.8	0.97	40	55	<5	0.29	<1	7	61	410	2.13	<10	0.66	134	<1	0.05	5	100	50	5	<20	19	<0.01	<10	1	<10	2	81
10	137960	0.6	0.31	95	10	<5	0.22	20	9	88	525	8.69	20	0.16	<1	<1	0.02	4	130	668	20	<20	27	<0.01	<10	1	<10	5	5205
19	137969	0.2	0.49	25	30	5	0.18	<1	5	63	13	2.96	<10	0.36	70	2	0.02	6	320	24	<5	<20	7	<0.01	<10	1	<10	3	51
36	137986	0.9	2.25	10	95	5	1.17	<1	11	94	19	2.63	<10	1.93	310	1	0.08	39	510	60	<5	<20	28	0.03	<10	15	<10	8	135
45	137995	14.3	0.18	180	30	<5	0.09	9	4	51	401	0.88	<10	0.04	3	2	<0.01	2	60	1180	60	<20	109	<0.01	<10	<1	<10	<1	2803
54	138054	0.7	0.19	<5	10	<5	0.29	<1	8	108	18	3.44	<10	0.09	35	<1	<0.01	5	180	8	5	<20	6	<0.01	<10	<1	<10	3	39
Standard:																													
GEO '03		1.6	1.53	60	130	5	1.65	<1	21	61	83	3.73	<10	0.91	628	<1	0.02	31	720	20	<5	<20	30	0.10	<10	58	<10	11	72
GEO '03		1.7	1.54	70	140	5	1.73	<1	22	62	85	3.83	<10	0.93	652	<1	0.02	32	720	22	5	<20	31	0.10	<10	57	<10	11	71

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
dl/5033
XLS/03

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-402

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

2-Oct-03

ATTENTION: **Bob Carmichael**

No. of samples received: 20
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 25
Samples submitted by: Shane

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	138066	0.15	0.004
2	138067	<0.03	<0.001
3	138068	0.11	0.003
4	138069	0.22	0.006
5	138070	0.27	0.008
6	138071	0.43	0.013
7	138072	0.14	0.004
8	138073	0.13	0.004
9	138074	0.10	0.003
10	138075	0.06	0.002
11	138076	0.08	0.002
12	138077	<0.03	<0.001
13	138078	0.21	0.006
14	138079	0.16	0.005
15	138080	0.05	0.001
16	138081	<0.03	<0.001
17	138082	<0.03	<0.001
18	138083	0.03	0.001
19	138084	<0.03	<0.001
20	138085	<0.03	<0.001
QC DATA:			
Repeat:			
1	138066	0.15	0.004
10	138075	0.06	0.002
Resplit:			
1	138066	0.15	0.004
Standard:			
PG102		0.07	0.002

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC DATA:																													
Resplit:																													
1	138066	1.4	2.89	65	15	<5	1.28	<1	23	126	2006	6.49	<10	1.92	280	11	0.13	126	840	120	<5	<20	108	0.50	<10	26	<10	6	750
Repeat:																													
1	138066	1.4	2.90	70	15	<5	1.29	1	22	127	2011	6.28	<10	1.88	266	12	0.14	123	720	130	20	<20	116	0.47	<10	30	<10	6	785
10	138075	0.7	0.92	20	40	5	0.74	<1	7	88	12	3.41	<10	0.47	111	4	0.07	6	280	30	10	<20	30	0.02	<10	3	<10	4	35
19	138084	0.2	0.22	50	<5	<5	0.52	<1	21	80	108	7.38	<10	0.22	154	<1	<0.01	7	1000	12	<5	<20	18	<0.01	<10	6	<10	6	26
Standard:																													
GEO '03		1.6	1.42	60	145	<5	1.82	<1	21	63	77	3.97	<10	0.87	694	11	0.01	36	800	20	15	<20	46	0.59	<10	67	<10	10	69

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
df/5035b
XLS/03

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-420

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

30-Sep-03

ATTENTION: Bob Carmichael

No. of samples received: 20
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 26
Samples submitted by: S.C.

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	138086	0.03	0.001	0.1	<0.01	<0.01	<0.01	<0.01
2	138087	<0.03	<0.001	0.2	0.01	0.01	0.01	0.02
3	138088	<0.03	<0.001	0.1	<0.01	0.01	<0.01	0.02
4	138089	<0.03	<0.001	0.4	0.01	0.02	0.01	0.02
5	138090	0.04	0.001	0.6	0.02	0.02	0.01	0.03
6	138091	2.09	0.061	146	4.26	0.64	0.42	1.01
7	138092	<0.03	<0.001	0.3	0.01	0.01	<0.01	0.03
8	138093	0.32	0.009	3.2	0.09	0.03	<0.01	0.01
9	138094	2.05	0.060	308	8.98	1.46	10.5	14.1
10	138095	1.06	0.031	36.5	1.06	0.46	0.01	0.06
11	138096	1.85	0.054	76.9	2.24	1.16	0.02	1.66
12	138097	2.15	0.063	78.3	2.28	1.79	0.02	0.51
13	138098	1.01	0.029	46.5	1.36	1.23	0.01	0.13
14	138099	2.12	0.062	80.9	2.36	3.96	0.02	0.45
15	138100	1.38	0.040	78.7	2.30	1.25	2.98	23.6
16	138101	1.82	0.053	110	3.21	1.41	0.91	25.1
17	138102	0.93	0.027	62.3	1.82	1.02	0.01	0.69
18	138103	0.15	0.004	1.1	0.03	0.01	<0.01	0.01
19	138104	0.17	0.005	0.8	0.02	0.01	0.01	0.01
20	138105	0.08	0.002	1.2	0.04	<0.01	<0.01	0.02

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. AK3-420

30-Sep-03

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
QC DATA:								
Resplit:								
1	138086	<0.03	<0.001	0.1	<0.01	<0.01	<0.01	<0.01
Repeat:								
10	138095	0.89	0.026					
11	138096	1.74	0.051					
12	138097	1.97	0.057					
13	138098	0.95	0.028					
14	138099	2.54	0.074					
15	138100	1.09	0.032					
16	138101	1.86	0.054					
17	138102	0.83	0.024					
Standard:								
PG102		0.07	0.002	-	-	-	-	-
PB106		-	-	60.3	1.76	0.62	0.53	0.84

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK3-420

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

30-Sep-03

ATTENTION: **Bob Carmichael**

ET #.	Tag #	SG g/cm^3
1	138086	2.65
2	138087	2.66
3	138088	2.67
4	138089	2.67
5	138090	2.66
7	138092	2.68
8	138093	4.21
10	138095	4.28
11	138096	4.24
12	138097	4.27
13	138098	4.14
14	138099	3.98
15	138100	4.08
16	138101	3.81
17	138102	3.23
18	138103	2.89
19	138104	2.79
20	138105	2.76

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

30-Sep-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-420

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 20
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 26
Samples submitted by: S.C.

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	138086	<0.2	2.58	<5	305	<5	1.24	<1	4	62	19	1.43	<10	1.24	317	2	0.26	11	410	22	<5	<20	72	0.03	<10	<1	<10	4	67
2	138087	0.2	2.18	10	165	<5	0.93	<1	5	62	73	1.76	<10	1.11	227	2	0.20	9	210	78	<5	<20	95	0.03	<10	<1	<10	2	150
3	138088	<0.2	2.94	5	200	5	1.33	<1	4	47	61	2.58	<10	1.54	226	<1	0.18	11	160	40	10	<20	318	0.04	<10	<1	<10	2	200
4	138089	0.5	1.60	30	55	<5	0.56	<1	9	51	138	2.35	<10	0.90	144	2	0.10	10	230	82	15	<20	127	0.05	<10	<1	<10	5	243
5	138090	0.6	1.87	25	40	<5	0.73	<1	9	66	159	2.67	<10	1.33	293	<1	0.12	15	280	92	15	<20	168	0.04	<10	7	<10	5	280
6	138091	>30	1.55	575	15	<5	0.18	45	5	26	6363	3.27	<10	1.70	210	<1	0.05	8	420	4220	245	<20	12	<0.01	<10	1	<10	<1	>10000
7	138092	0.3	2.36	30	50	<5	0.58	<1	7	75	105	2.57	<10	1.83	261	2	0.13	13	230	46	<5	<20	94	0.03	<10	5	<10	2	271
8	138093	3.1	0.66	55	25	<5	0.45	<1	6	82	189	>10	20	0.43	<1	<1	0.06	4	40	24	5	<20	42	<0.01	<10	<1	<10	1	114
9	138094	>30	0.12	1725	10	<5	0.11	801	3	23	>10000	4.28	<10	0.13	25	<1	0.01	<1	430	>10000	880	<20	21	<0.01	<10	2	<10	<1	>10000
10	138095	>30	0.45	1180	<5	<5	0.24	<1	7	101	4206	>10	30	0.45	<1	<1	0.02	2	170	120	50	<20	14	<0.01	<10	<1	<10	4	456
11	138096	>30	0.44	2045	10	<5	0.15	51	7	87	>10000	>10	20	0.50	<1	<1	0.02	<1	340	164	85	<20	11	<0.01	<10	<1	<10	2	>10000
12	138097	>30	0.40	4305	115	<5	0.13	<1	<1	86	>10000	>10	20	0.54	<1	32	0.02	62	<10	189	340	<20	72	<0.01	<10	2	<10	<1	4920
13	138098	>30	0.75	2385	65	<5	0.20	<1	<1	79	>10000	>10	20	0.90	<1	28	0.02	59	<10	90	305	<20	48	<0.01	<10	4	<10	<1	1213
14	138099	>30	0.87	1840	40	<5	1.02	26	7	84	>10000	>10	20	1.25	<1	28	0.02	58	580	202	320	<20	8	<0.01	<10	2	<10	<1	3929
15	138100	>30	0.53	1385	<5	<5	0.07	>1000	6	59	>10000	>10	<10	0.85	<1	<1	<0.01	5	270	>10000	195	<20	16	<0.01	<10	<1	<10	1	>10000
16	138101	>30	0.58	3430	55	<5	0.10	>1000	5	55	>10000	>10	10	0.94	19	71	<0.01	47	170	9470	635	<20	22	<0.01	<10	1	<10	<1	>10000
17	138102	>30	1.88	2365	10	<5	0.38	24	9	84	>10000	>10	20	2.64	124	3	0.03	6	230	68	135	<20	14	<0.01	<10	6	<10	2	6676
18	138103	1.2	0.55	40	<5	<5	0.49	<1	9	114	161	9.21	10	0.58	<1	4	0.02	18	80	36	10	<20	13	<0.01	<10	3	<10	2	135
19	138104	0.9	1.03	40	<5	5	0.46	<1	17	118	95	6.79	<10	1.08	43	5	0.04	94	300	60	10	<20	8	0.01	<10	12	<10	4	115
20	138105	1.2	2.07	70	10	5	1.39	<1	17	158	46	6.25	<10	1.62	302	6	0.13	68	800	58	10	<20	35	0.05	<10	17	<10	4	164

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC DATA:																													
Resplit:																													
1	138086	<0.2	2.62	<5	325	<5	1.36	<1	4	56	20	1.52	<10	1.24	340	1	0.26	9	440	24	<5	<20	71	0.04	<10	<1	<10	5	69
Repeat:																													
1	138086	<0.2	2.60	<5	305	<5	1.27	<1	4	63	22	1.42	<10	1.22	319	3	0.27	10	420	26	<5	<20	74	0.04	<10	<1	<10	5	70
10	138095	>30	0.45	1170	<5	<5	0.25	<1	7	96	4297	>10	20	0.43	<1	<1	0.03	4	160	134	55	<20	13	<0.01	<10	<1	<10	2	460
19	138104	0.7	1.06	50	<5	<5	0.47	<1	17	121	92	6.88	<10	1.09	48	6	0.04	96	320	64	10	<20	6	0.01	<10	12	<10	4	107
Standard:																													
GEO'03		1.6	1.57	55	140	<5	1.65	<1	19	55	83	3.45	10	0.94	645	<1	0.02	27	650	20	<5	<20	46	0.08	<10	64	<10	9	72

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
df/420
XLS/03

OCT 2 0 2003

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-433

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

10-Oct-03

ATTENTION: Bob Carmichael

No. of samples received: 55
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 27
Samples submitted by: S.C.

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	E03210	<0.03	<0.001
2	E03211	<0.03	<0.001
3	E03212	<0.03	<0.001
4	E03213	<0.03	<0.001
5	E03214	0.11	0.003
6	E03215	0.08	0.002
7	E03216	0.09	0.003
8	E03217	0.09	0.003
9	E03218	2.07	0.060
10	E03219	0.05	0.001
11	E03220	0.05	0.001
12	E03221	<0.03	<0.001
13	E03222	0.07	0.002
14	E03223	0.33	0.010
15	E03224	0.35	0.010
16	E03225	0.06	0.002
17	E03226	<0.03	<0.001
18	E03227	<0.03	<0.001
19	E03228	0.07	0.002
20	E03229	<0.03	<0.001
21	E03230	<0.03	<0.001
22	E03231	<0.03	<0.001
23	E03232	<0.03	<0.001
24	E03233	0.10	0.003
25	E03234	<0.03	<0.001
26	E03235	<0.03	<0.001
27	E03236	0.35	0.010
28	E03237	0.56	0.016

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. **AK3-433** 10-Oct-03

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	E03238	0.52	0.015
30	E03239	0.12	0.003
31	E03240	0.12	0.003
32	E03241	0.09	0.003
33	E03242	<0.03	<0.001
34	E03243	0.08	0.002
35	E03244	0.21	0.006
36	E03245	0.24	0.007
37	E03246	0.07	0.002
38	E03247	0.33	0.010
39	E03248	0.21	0.006
40	E03249	0.09	0.003
41	E03250	0.20	0.006
42	E03251	0.29	0.008
43	E03252	2.11	0.062
44	E03253	0.22	0.006
45	E03254	0.14	0.004
46	E03255	0.10	0.003
47	E03256	0.40	0.012
48	E03203	0.35	0.010
49	E03204	0.08	0.002
50	E03205	0.04	0.001
51	E03206	0.04	0.001
52	E03207	<0.03	<0.001
53	E03208	<0.03	<0.001
54	E03209	0.04	0.001
55	138106	0.16	0.005
QC DATA:			
Repeat:			
1	E03210	<0.03	<0.001
10	E03219	0.03	0.001
19	E03228	0.09	0.003
36	E03245	0.26	0.008
45	E03254	0.12	0.003
Resplit:			
1	E03210	<0.03	<0.001
36	E03245	0.22	0.006
Standard:			
PM184		0.51	0.015
PM184		0.52	0.015

JJ/lh
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

10-Oct-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-433

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 55
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 27
Samples submitted by: S.C.

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	E03210	0.8	0.20	5	15	<5	0.10	<1	12	104	11	4.80	10	0.12	<1	4	0.02	4	120	22	<5	<20	6	<0.01	<10	<1	<10	2	48
2	E03211	0.3	2.86	85	60	<5	2.91	<1	44	243	69	2.88	<10	3.17	272	<1	0.06	412	830	36	<5	<20	96	0.10	<10	16	<10	5	28
3	E03212	<0.2	2.08	10	105	5	1.70	<1	24	70	28	3.17	20	1.22	316	3	0.24	32	780	22	<5	<20	120	0.16	<10	40	<10	9	42
4	E03213	0.3	0.42	5	30	<5	1.01	<1	6	121	9	2.45	<10	0.31	74	6	0.03	18	140	12	5	<20	20	<0.01	<10	3	<10	1	16
5	E03214	0.8	0.31	15	20	10	0.13	<1	7	50	12	3.66	10	0.11	<1	7	0.02	2	250	16	5	<20	5	<0.01	<10	1	<10	2	22
6	E03215	0.7	0.22	30	25	<5	0.11	<1	8	107	14	2.93	<10	0.10	<1	10	0.02	4	70	10	5	<20	7	<0.01	<10	2	<10	1	47
7	E03216	2.3	0.44	40	20	5	0.24	<1	9	92	24	4.44	10	0.24	<1	5	0.04	5	140	24	5	<20	8	<0.01	<10	3	<10	2	39
8	E03217	4.2	0.26	60	<5	10	0.14	<1	9	100	28	8.37	20	0.19	<1	4	0.02	4	190	42	15	<20	5	<0.01	<10	1	<10	2	35
9	E03218	>30	0.11	1905	10	<5	0.11	771	5	23	>10000	4.50	<10	0.14	28	<1	0.02	<1	370	>10000	1100	<20	14	<0.01	<10	4	<10	<1	>10000
10	E03219	1.4	0.22	15	<5	<5	0.14	<1	17	95	22	>10	30	0.26	<1	<1	0.02	1	160	18	10	<20	6	<0.01	<10	1	<10	3	93
11	E03220	1.2	0.29	30	10	5	0.22	<1	11	90	18	8.19	20	0.24	<1	6	0.02	2	200	12	10	<20	7	<0.01	<10	3	<10	2	91
12	E03221	0.4	0.47	<5	20	<5	0.87	<1	5	102	12	5.01	10	0.53	218	2	0.02	6	60	22	5	<20	5	<0.01	<10	4	<10	2	43
13	E03222	0.7	0.79	20	15	<5	1.12	<1	13	68	17	9.86	20	0.89	179	13	0.02	5	280	10	5	<20	16	<0.01	<10	3	<10	5	52
14	E03223	1.0	0.54	45	15	5	0.34	<1	9	76	22	8.10	20	0.47	36	11	0.02	3	190	14	<5	<20	20	<0.01	<10	2	<10	3	85
15	E03224	1.4	0.47	60	10	5	0.34	<1	8	81	22	7.67	20	0.41	22	10	0.02	3	180	20	5	<20	25	<0.01	<10	2	<10	3	57
16	E03225	0.3	0.21	15	20	5	0.17	<1	5	90	35	3.38	<10	0.13	14	20	0.01	3	80	4	5	<20	19	<0.01	<10	1	<10	1	17
17	E03226	<0.2	0.21	<5	25	<5	0.30	<1	4	101	8	2.66	<10	0.13	31	6	0.01	4	120	<2	<5	<20	6	<0.01	<10	1	<10	2	11
18	E03227	<0.2	0.23	<5	25	<5	0.23	<1	5	82	6	2.80	<10	0.15	34	3	0.01	3	140	<2	<5	<20	7	<0.01	<10	1	<10	1	11
19	E03228	0.9	0.44	50	10	25	0.26	<1	16	70	42	8.32	20	0.40	<1	11	0.02	9	330	10	10	<20	10	<0.01	<10	2	<10	3	22
20	E03229	0.2	0.95	10	20	<5	0.28	<1	10	83	8	5.80	20	1.02	160	2	0.02	4	260	2	<5	<20	13	<0.01	<10	2	<10	2	32
21	E03230	0.2	0.45	5	25	<5	0.13	<1	4	121	6	3.17	<10	0.47	76	8	0.01	4	80	6	<5	<20	7	<0.01	<10	1	<10	1	17
22	E03231	0.4	1.10	15	35	<5	0.36	<1	7	78	15	4.04	10	1.24	258	7	0.01	8	120	24	<5	<20	12	<0.01	<10	4	<10	2	44
23	E03232	<0.2	0.36	<5	730	<5	3.45	<1	16	58	14	3.92	40	1.91	816	<1	0.04	22	2280	6	5	<20	326	<0.01	<10	22	<10	7	86
24	E03233	0.5	0.32	85	10	<5	3.93	<1	57	88	15	>10	30	2.64	827	<1	0.02	17	700	44	<5	<20	245	<0.01	<10	8	<10	7	64
25	E03234	<0.2	1.18	<5	40	<5	0.55	1	8	62	4	2.89	<10	1.77	372	9	0.02	8	310	22	<5	<20	37	<0.01	<10	2	<10	2	54

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	E03235	<0.2	1.20	<5	50	<5	0.58	<1	5	63	3	2.14	<10	1.66	442	7	0.02	7	290	12	5	<20	53	<0.01	<10	2	<10	3	36
27	E03236	2.1	0.89	120	20	<5	0.70	<1	14	47	60	4.77	10	1.27	321	8	0.02	13	140	58	30	<20	51	<0.01	<10	4	<10	3	98
28	E03237	6.2	0.38	215	5	<5	0.49	<1	22	70	324	>10	20	0.40	17	17	0.01	19	120	158	90	<20	23	<0.01	<10	6	<10	3	110
29	E03238	4.3	0.32	205	<5	<5	0.31	<1	26	56	182	8.84	10	0.30	<1	13	0.01	18	110	112	50	<20	20	<0.01	<10	4	<10	3	86
30	E03239	0.6	0.92	100	30	<5	1.01	<1	15	80	59	3.97	<10	0.85	223	2	0.05	23	370	46	25	<20	50	<0.01	<10	11	<10	3	88
31	E03240	0.9	0.20	45	5	<5	0.32	<1	16	94	57	8.56	10	0.23	<1	<1	0.01	29	70	166	15	<20	21	<0.01	<10	2	<10	2	227
32	E03241	2.0	0.19	90	20	<5	0.29	7	18	94	203	4.50	<10	0.15	51	<1	0.01	31	220	724	55	<20	19	<0.01	<10	2	<10	2	1853
33	E03242	<0.2	1.94	5	120	5	1.71	<1	26	85	32	3.36	10	1.19	359	3	0.21	31	810	34	<5	<20	102	0.17	<10	41	<10	9	58
34	E03243	0.8	0.21	195	<5	<5	0.38	<1	28	107	67	8.94	10	0.22	<1	<1	0.01	31	480	70	15	<20	24	<0.01	<10	3	<10	4	166
35	E03244	1.9	0.21	220	<5	<5	0.32	3	25	106	565	>10	30	0.30	<1	<1	0.01	4	510	42	10	<20	17	<0.01	<10	2	<10	5	1812
36	E03245	1.9	0.35	160	15	<5	1.30	33	15	64	654	7.21	10	0.59	365	<1	0.02	11	780	44	100	<20	84	<0.01	<10	6	<10	6	7802
37	E03246	0.5	0.37	40	40	<5	5.29	8	7	74	69	2.88	<10	2.17	1462	<1	0.02	29	60	12	10	<20	501	<0.01	<10	6	<10	6	1572
38	E03247	0.8	0.64	535	45	<5	4.13	1	30	77	93	4.40	<10	1.80	1332	<1	0.02	258	530	32	55	<20	375	<0.01	<10	15	<10	6	818
39	E03248	1.4	0.34	200	20	<5	0.32	<1	16	69	307	4.81	10	0.21	51	2	0.01	29	290	26	20	<20	23	<0.01	<10	4	<10	3	552
40	E03249	0.9	0.31	150	20	<5	0.35	2	15	67	310	3.49	<10	0.18	88	<1	0.01	11	440	20	25	<20	58	<0.01	<10	3	<10	3	870
41	E03250	0.9	0.30	220	10	<5	0.29	1	19	78	275	5.36	10	0.14	7	1	0.01	18	600	38	20	<20	9	<0.01	<10	4	<10	3	659
42	E03251	1.0	0.21	225	10	<5	0.27	<1	11	86	49	6.86	10	0.13	<1	<1	0.01	3	740	44	5	<20	6	<0.01	<10	4	<10	3	126
43	E03252	>30	1.49	580	25	<5	0.21	46	7	26	6105	3.54	<10	1.67	226	<1	0.04	6	520	4592	280	<20	15	<0.01	<10	4	<10	3	>10000
44	E03253	2.1	0.21	135	15	<5	0.14	2	12	125	824	4.98	<10	0.11	9	4	0.01	5	270	76	5	<20	8	<0.01	<10	5	<10	2	658
45	E03254	0.7	0.16	95	10	<5	0.21	<1	10	116	92	5.19	<10	0.10	17	<1	0.01	4	350	36	15	<20	15	<0.01	<10	4	<10	2	44
46	E03255	1.0	0.23	75	10	<5	0.27	<1	21	93	115	4.59	<10	0.12	23	2	0.02	8	320	96	50	<20	13	<0.01	<10	7	<10	2	153
47	E03256	1.6	0.23	210	<5	<5	0.42	<1	35	90	95	>10	20	0.19	<1	<1	0.01	9	420	56	25	<20	8	<0.01	<10	10	<10	2	328
48	E03203	5.3	0.37	305	15	<5	0.12	<1	16	117	69	5.83	10	0.15	<1	6	0.03	3	50	50	20	<20	6	<0.01	<10	1	<10	2	200
49	E03204	1.5	0.46	20	<5	5	0.23	<1	11	93	17	>10	20	0.29	<1	10	0.03	4	200	58	10	<20	10	<0.01	<10	1	<10	4	69
50	E03205	1.8	0.42	75	15	<5	0.20	<1	9	128	243	5.34	10	0.17	<1	9	0.03	5	170	18	70	<20	7	<0.01	<10	2	<10	2	92
51	E03206	0.5	0.33	20	5	<5	0.16	<1	17	80	32	9.27	20	0.19	<1	3	0.03	5	200	6	10	<20	8	<0.01	<10	1	<10	3	18
52	E03207	0.4	0.42	15	15	<5	0.24	<1	19	125	32	6.09	10	0.20	<1	4	0.03	5	120	6	10	<20	9	<0.01	<10	2	<10	2	24
53	E03208	<0.2	4.51	25	135	10	2.58	<1	50	386	73	3.94	<10	4.30	433	2	0.11	309	1280	30	<5	<20	76	0.19	<10	55	<10	10	81
54	E03209	0.8	0.38	10	<5	<5	0.24	<1	17	102	19	9.22	20	0.21	<1	2	0.03	5	210	10	<5	<20	7	<0.01	<10	1	<10	4	28
55	138106	3.2	0.48	130	5	5	0.19	<1	16	70	77	8.84	20	0.30	<1	2	0.03	11	170	88	15	<20	11	<0.01	<10	3	<10	3	161

QC DATA:

Resplit:

1	E03210	0.9	0.19	10	10	<5	0.10	<1	12	112	12	5.16	<10	0.11	<1	5	0.02	5	110	22	5	<20	5	<0.01	<10	<1	<10	2	58
36	E03245	2.1	0.38	165	15	<5	1.34	35	16	73	718	7.81	20	0.60	361	<1	0.02	10	830	42	110	<20	81	<0.01	<10	6	<10	5	8465

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
Repeat:																													
1	E03210	1.0	0.19	10	10	<5	0.09	<1	12	102	21	4.79	10	0.11	<1	4	0.02	3	120	38	5	<20	6	<0.01	<10	<1	<10	2	183
10	E03219	1.5	0.21	20	<5	5	0.14	<1	17	95	21	>10	30	0.26	<1	<1	0.02	2	160	18	5	<20	6	<0.01	<10	1	<10	3	86
19	E03228	0.9	0.40	60	10	10	0.27	<1	15	71	38	8.40	10	0.37	<1	12	0.01	11	290	12	15	<20	10	<0.01	<10	2	<10	3	22
36	E03245	2.0	0.33	165	15	<5	1.30	34	15	63	661	7.22	10	0.60	364	<1	0.02	10	800	42	110	<20	83	<0.01	<10	6	<10	5	7775
45	E03254	0.7	0.16	95	5	<5	0.21	<1	10	112	89	5.13	<10	0.12	21	<1	0.01	8	330	32	20	<20	13	<0.01	<10	4	<10	2	40
54	E03209	0.8	0.40	15	10	5	0.24	<1	17	102	19	9.23	20	0.21	<1	3	0.03	4	200	8	5	<20	7	<0.01	<10	1	<10	4	28
Standard:																													
GEO '03		1.4	1.58	65	140	<5	1.67	<1	20	58	81	3.66	10	0.93	644	<1	0.03	31	640	24	5	<20	37	0.10	<10	64	<10	10	78
GEO '03		1.5	1.60	60	140	<5	1.67	<1	21	59	82	3.65	10	0.92	643	<1	0.03	29	680	24	5	<20	38	0.11	<10	60	<10	11	80

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/lh
df/436
XLS/03

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-448

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

23-Oct-03

ATTENTION: **Bob Carmichael**

No. of samples received: 41
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 28
Samples submitted by: SC

ET #.	Tag #	SG g/cm^3
4	E03260	3.03
5	E03261	3.12

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-448

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

22-Oct-03

ATTENTION: Bob Carmichael

No. of samples received: 41
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 28
Samples submitted by: SC

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	E03257	<0.03	<0.001					
2	E03258	<0.03	<0.001					
3	E03259	0.26	0.008					
4	E03260	0.84	0.024	14.6	0.43	0.73	0.19	2.51
5	E03261	0.50	0.015	16.5	0.48	0.65	0.19	6.19
6	E03262	0.11	0.003					
7	E03263	0.49	0.014					
8	E03264	0.04	0.001					
9	E03265	0.94	0.027					
10	E03266	0.03	0.001					
11	E03267	<0.03	<0.001					
12	E03268	<0.03	<0.001					
13	E03269	<0.03	<0.001					
14	E03270	<0.03	<0.001					
15	E03271	0.03	0.001					
16	E03272	0.06	0.002					
17	E03273	0.09	0.003					
18	E03274	0.26	0.008					
19	E03275	0.29	0.008					
20	E03276	1.07	0.031					
21	E03277	0.90	0.026					
22	E03278	0.08	0.002					
23	E03279	<0.03	<0.001					
24	E03280	0.03	0.001					
25	E03281	0.03	0.001					
26	E03282	0.19	0.006					
27	E03283	0.05	0.001					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. AK3-448 22-Oct-03

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
28	E03284	0.13	0.004					
29	E03285	0.20	0.006					
30	E03286	0.06	0.002					
31	E03287	<0.03	<0.001					
32	E03288	<0.03	<0.001					
33	E03289	0.06	0.002					
34	E03290	0.20	0.006					
35	E03291	2.10	0.061	138	4.02	0.62	0.47	1.05
36	E03292	<0.03	<0.001					
37	E03293	<0.03	<0.001					
38	E03294	2.04	0.059	308	8.98	1.50	10.6	14.1
39	E03295	0.03	0.001					
40	E03296	<0.03	<0.001					
41	E03297	<0.03	<0.001					
QC DATA:								
Repeat:								
1	E03257	<0.03	<0.001					
4	E03260	0.86	0.025					
9	E03265	1.05	0.031					
10	E03266	0.03	0.001					
19	E03275	0.28	0.008					
20	E03276	1.14	0.033					
36	E03292	0.04	0.001					
Resplit:								
1	E03257	<0.03	<0.001					
36	E03292	0.04	0.001					
Standard:								
PM184		0.52	0.015					
PM184		0.51	0.015					

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

22-Oct-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-448

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 41
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 28
Samples submitted by: SC

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	E03257	<0.2	2.54	<5	165	<5	1.26	<1	6	50	19	1.62	<10	1.20	363	<1	0.19	10	390	54	15	<20	71	0.04	<10	<1	<10	7	93
2	E03258	<0.2	1.91	<5	160	<5	1.02	<1	4	41	6	1.27	<10	0.90	240	<1	0.15	8	370	26	<5	<20	50	0.02	<10	<1	<10	5	60
3	E03259	5.5	1.52	5	40	<5	1.88	8	6	53	186	1.60	<10	0.70	203	6	0.11	12	400	212	10	<20	107	0.01	<10	5	<10	5	1299
4	E03260	14.4	0.31	70	<5	<5	1.60	92	7	61	7434	7.42	<10	0.28	91	2	0.02	5	610	1722	85	<20	29	<0.01	<10	3	<10	3	>10000
5	E03261	16.3	0.12	830	<5	<5	0.40	263	4	22	6591	2.80	<10	0.05	<1	<1	0.01	<1	490	1726	840	<20	32	<0.01	<10	<1	<10	1	>10000
6	E03262	2.4	0.09	125	20	<5	0.13	49	2	81	779	0.72	<10	0.02	17	<1	<0.01	<1	70	1728	110	<20	56	<0.01	<10	<1	<10	<1	9494
7	E03263	2.9	0.13	135	<5	<5	0.30	<1	9	61	224	3.98	<10	0.06	<1	3	0.01	10	30	72	30	<20	20	<0.01	<10	<1	<10	1	390
8	E03264	0.4	0.31	5	105	<5	3.70	<1	15	54	193	4.04	20	1.55	778	1	0.03	21	2570	14	<5	<20	271	<0.01	<10	19	<10	9	235
9	E03265	2.8	0.31	225	<5	<5	1.96	<1	46	64	40	9.42	<10	0.68	272	<1	0.01	65	210	110	<5	<20	151	<0.01	<10	3	<10	6	65
10	E03266	0.2	0.17	130	135	<5	0.83	<1	<1	77	6	0.53	<10	0.03	515	5	0.04	4	60	32	<5	<20	27	<0.01	<10	<1	<10	3	48
11	E03267	<0.2	1.88	5	125	<5	1.64	<1	18	82	35	3.32	<10	1.20	336	5	0.16	32	1070	30	<5	<20	98	0.16	<10	44	<10	5	52
12	E03268	0.2	0.26	230	80	<5	0.89	<1	<1	70	2	0.60	<10	0.03	519	2	0.04	5	50	52	<5	<20	26	<0.01	<10	<1	<10	3	31
13	E03269	<0.2	0.27	90	50	<5	0.65	<1	1	77	3	0.51	<10	0.06	441	5	0.05	5	50	34	10	<20	22	<0.01	<10	<1	<10	4	43
14	E03270	<0.2	0.32	105	60	<5	0.68	<1	1	65	4	0.58	<10	0.09	474	2	0.04	4	60	38	5	<20	24	<0.01	<10	<1	<10	4	45
15	E03271	<0.2	0.29	<5	<5	<5	0.35	<1	8	113	19	4.43	<10	0.39	52	6	0.01	5	150	24	5	<20	13	<0.01	<10	1	<10	2	49
16	E03272	0.4	0.23	5	<5	<5	0.24	<1	14	96	30	6.87	<10	0.32	<1	6	0.01	3	100	20	<5	<20	8	<0.01	<10	<1	<10	3	49
17	E03273	0.7	0.65	<5	<5	<5	0.61	<1	16	125	21	7.06	<10	0.93	83	11	0.01	41	310	18	<5	<20	9	<0.01	<10	6	<10	4	52
18	E03274	1.8	0.34	15	<5	<5	0.38	<1	9	51	58	5.64	<10	0.38	6	4	0.01	4	110	32	<5	<20	26	<0.01	<10	1	<10	3	55
19	E03275	2.4	0.16	35	<5	<5	0.20	<1	8	61	21	6.31	<10	0.15	<1	3	0.01	3	30	104	5	<20	9	<0.01	<10	<1	<10	3	29
20	E03276	3.5	0.17	170	<5	5	0.17	<1	10	47	37	7.07	<10	0.13	<1	3	0.01	2	<10	72	10	<20	10	<0.01	<10	<1	<10	3	16
21	E03277	2.9	0.17	75	<5	<5	0.10	<1	9	49	27	4.35	<10	0.09	<1	5	0.01	3	<10	16	5	<20	7	<0.01	<10	<1	<10	2	12
22	E03278	0.6	0.38	30	25	<5	1.36	<1	6	80	40	2.88	<10	0.41	386	4	0.02	12	250	26	10	<20	50	<0.01	<10	3	<10	3	65
23	E03279	0.3	0.58	<5	45	<5	1.37	<1	3	75	33	1.38	<10	0.36	339	3	0.04	7	240	54	<5	<20	34	<0.01	<10	5	<10	5	93
24	E03280	0.3	1.79	5	85	<5	1.11	<1	4	66	33	1.84	<10	0.63	268	1	0.16	8	310	54	10	<20	55	0.03	<10	1	<10	4	202
25	E03281	0.2	1.84	<5	145	<5	1.00	<1	5	67	20	1.79	<10	0.63	212	2	0.15	8	310	50	15	<20	112	0.02	<10	1	<10	3	266

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	E03282	2.1	0.81	90	10	<5	0.72	1	6	47	54	2.82	<10	0.44	91	1	0.05	4	340	204	15	<20	100	<0.01	<10	3	<10	9	570
27	E03283	0.7	1.65	<5	35	<5	0.65	1	5	58	43	2.12	<10	1.50	269	2	0.07	7	430	58	<5	<20	41	<0.01	<10	3	<10	6	391
28	E03284	1.9	1.15	120	20	<5	0.58	8	6	47	144	2.49	<10	0.71	90	2	0.08	5	330	1090	25	<20	39	<0.01	<10	2	<10	5	1925
29	E03285	2.2	1.26	140	5	<5	0.87	<1	8	53	804	3.74	<10	0.80	136	10	0.10	7	540	186	60	<20	45	<0.01	<10	3	<10	6	352
30	E03286	0.3	0.49	30	<5	<5	0.77	<1	16	67	54	4.02	<10	0.35	27	5	0.03	5	390	28	5	<20	63	<0.01	<10	2	<10	4	22
31	E03287	0.2	1.39	30	85	<5	1.02	<1	5	74	12	1.62	<10	1.25	272	2	0.04	18	330	32	5	<20	30	<0.01	<10	5	<10	3	66
32	E03288	<0.2	2.14	10	35	<5	1.45	<1	9	145	8	2.71	<10	1.97	343	4	0.06	70	560	38	5	<20	39	0.01	<10	10	<10	4	71
33	E03289	0.5	5.79	95	45	<5	3.98	<1	69	316	102	4.83	<10	3.90	858	<1	0.24	211	1220	74	<5	<20	113	0.09	<10	157	<10	4	160
34	E03290	1.1	0.72	70	15	<5	1.04	<1	7	59	31	2.35	<10	0.42	112	4	0.04	11	330	30	10	<20	28	<0.01	<10	7	<10	3	44
35	E03291	>30	1.37	660	5	<5	0.22	47	8	29	6136	3.78	<10	1.56	215	<1	0.03	9	1120	4680	255	<20	16	<0.01	<10	3	<10	3	>10000
36	E03292	0.6	0.52	50	20	<5	0.85	<1	5	54	16	2.13	<10	0.41	132	1	0.02	5	280	24	10	<20	19	<0.01	<10	3	<10	3	21
37	E03293	0.2	0.69	20	20	<5	1.17	<1	5	50	14	2.17	<10	0.58	188	3	0.03	6	400	16	5	<20	21	<0.01	<10	3	<10	5	28
38	E03294	>30	0.09	2145	<5	<5	0.12	816	6	24	>10000	4.89	<10	0.12	24	<1	0.01	<1	1320	>10000	1095	<20	15	<0.01	<10	3	<10	2	>10000
39	E03295	0.3	1.00	5	40	<5	1.01	<1	6	64	20	2.09	<10	0.91	233	3	0.03	8	470	22	<5	<20	26	<0.01	<10	3	<10	4	74
40	E03296	1.1	0.79	15	50	<5	1.34	9	5	59	249	2.04	<10	0.71	263	2	0.02	10	400	36	10	<20	18	<0.01	<10	4	<10	4	318
41	E03297	0.9	1.58	30	70	<5	2.50	<1	7	70	167	2.27	<10	1.04	509	4	0.08	16	350	28	10	<20	26	<0.01	<10	10	<10	3	90
QC DATA:																													
Resplit:																													
1	E03257	<0.2	2.49	<5	160	<5	1.25	<1	5	47	19	1.54	<10	1.20	362	<1	0.19	10	400	54	10	<20	71	0.03	<10	<1	<10	7	91
36	E03292	0.6	0.50	50	20	<5	0.93	<1	5	52	20	2.25	<10	0.39	132	1	0.02	5	340	26	15	<20	17	<0.01	<10	3	<10	3	25
Repeat:																													
1	E03257	<0.2	2.53	<5	160	<5	1.27	<1	5	50	17	1.58	<10	1.22	361	<1	0.19	10	390	58	15	<20	71	0.04	<10	<1	<10	7	91
10	E03266	0.2	0.17	125	140	<5	0.82	<1	<1	75	5	0.51	<10	0.03	516	4	0.04	5	60	32	<5	<20	27	<0.01	<10	<1	<10	3	43
19	E03275	2.4	0.17	35	<5	<5	0.20	<1	9	64	21	6.58	<10	0.15	<1	3	0.01	2	30	112	<5	<20	9	<0.01	<10	<1	<10	3	33
36	E03292	0.7	0.52	50	20	<5	0.90	<1	5	57	16	2.24	<10	0.40	135	1	0.02	6	330	26	15	<20	16	<0.01	<10	3	<10	3	25
Standard:																													
GEO '03		1.5	1.56	60	135	<5	1.63	<1	20	59	81	3.57	<10	0.91	623	<1	0.02	31	940	22	<5	<20	49	0.10	<10	65	<10	8	77
GEO '03		1.4	1.49	70	140	<5	1.70	<1	20	60	78	3.71	<10	0.88	643	<1	0.02	34	860	24	<5	<20	45	0.09	<10	66	<10	8	80

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
df/448
XLS/03

NOV 5 2003

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-466

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

24-Oct-03

ATTENTION: Bob Carmichael

No. of samples received: 61
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 29
Samples submitted by: S.C.

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	E03298	1.90	0.055					
2	E03299	0.77	0.022	12.6	0.37	0.10	1.30	0.79
3	E03300	0.92	0.027	31.6	0.92	0.55	0.84	1.22
4	E03301	3.76	0.110	60.9	1.78	1.38	0.08	0.44
5	E03302	1.87	0.055					
6	E03303	3.99	0.116	38.7	1.13	0.23	1.00	4.40
7	E03304	1.06	0.031	10.7	0.31	0.04	0.47	1.10
8	E03305	0.08	0.002					
9	E03306	0.30	0.009					
10	E03307	0.37	0.011					
11	E03308	0.29	0.008	26.7	0.78	0.03	4.40	9.70
12	E03309	0.18	0.005	10.9	0.32	0.52	2.10	5.30
13	E03310	0.23	0.007	26.5	0.77	0.32	4.90	9.40
14	E03311	0.14	0.004	4.2	0.12	0.03	0.50	1.08
15	E03312	<0.03	<0.001					
16	E03313	0.24	0.007	27.1	0.79	0.01	2.20	5.30
17	E03314	0.68	0.020	29.2	0.85	0.04	1.24	3.20
18	E03315	0.16	0.005					
19	E03316	0.57	0.017					
20	E03317	0.63	0.018					
21	E03318	2.03	0.059	302	8.81	1.49	10.1	14.8
22	E03319	0.42	0.012					
23	E03320	1.15	0.034					
24	E03321	2.49	0.073					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
25	E03322	1.22	0.036	24.1	0.70	0.10	1.45	3.10
26	E03323	1.79	0.052					
27	E03324	1.64	0.048					
28	E03325	0.34	0.010					
29	E03326	0.16	0.005					
30	E03327	0.18	0.005					
31	E03328	0.06	0.002					
32	E03329	0.18	0.005					
33	E03330	0.26	0.008					
34	E03331	0.07	0.002					
35	E03332	<0.03	<0.001					
36	E03333	0.30	0.009					
37	E03334	0.31	0.009	1.9	0.06	0.78	0.01	1.30
38	E03335	0.37	0.011	4.5	0.13	1.05	0.02	1.70
39	E03336	0.14	0.004					
40	E03337	0.24	0.007					
41	E03338	0.19	0.006					
42	E03339	0.15	0.004	2.0	0.06	0.07	0.11	1.02
43	E03340	0.27	0.008					
44	E03341	0.07	0.002					
45	E03342	<0.03	<0.001					
46	E03343	0.08	0.002					
47	E03344	0.12	0.003					
48	E03345	0.15	0.004					
49	E03346	0.10	0.003					
50	E03347	<0.03	<0.001					
51	E03348	<0.03	<0.001					
52	E03349	0.20	0.006					
53	E03350	0.19	0.006					
54	E03351	0.10	0.003					
55	E03352	1.99	0.058	138	4.02	0.62	0.46	1.04
56	E03353	0.08	0.002					
57	E03354	0.07	0.002					
58	E03355	0.09	0.003					
59	E03356	0.04	0.001					
60	E03357	0.05	0.001					
61	E03358	0.19	0.006					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN **RESOURCES LTD. AK3-466** 24-Oct-03

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
QC DATA:								
Repeat:								
1	E03298	1.95	0.057					
4		3.23	0.094					
6		3.26	0.095					
10	E03307	0.38	0.011					
19	E03316	0.58	0.017					
24		2.39	0.070					
36	E03333	0.28	0.008					
45	E03342	<0.03	<0.001					
Resplit:								
1	E03298	2.11	0.062					
36	E03333	0.30	0.009					
Standard:								
PM163		1.72	0.050					
PM163		1.64	0.048					
PB106				58.1	1.69	0.62	0.52	0.87

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-466

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

24-Oct-03

ATTENTION: Bob Carmichael

No. of samples received: 61
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 29
Samples submitted by: S.C.

ET #.	Tag #	SG g/cm^3
2	E03299	2.88
3	E03300	2.89
4	E03301	3.23
6	E03303	3.53
7	E03304	2.99
11	E03308	3.16
12	E03309	2.95
13	E03310	3.06
14	E03311	2.88
16	E03313	3.48
17	E03314	3.83
25	E03322	3.17
37	E03334	2.88
38	E03335	2.89
42	E03339	2.78

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

23-Oct-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-466

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 61
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 29
Samples submitted by: S.C.

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	E03298	0.8	2.59	5	330	<5	1.19	<1	5	72	146	2.05	<10	1.26	249	2	0.21	11	330	88	<5	<20	264	0.04	<10	42	<10	3	304
2	E03299	11.7	0.43	30	35	<5	0.49	33	2	66	918	0.90	<10	0.14	50	<1	0.04	2	180	>10000	15	<20	90	<0.01	<10	12	<10	1	7275
3	E03300	>30	0.40	65	5	<5	0.69	63	6	45	5612	2.89	<10	0.14	1	17	0.03	<1	830	8758	10	<20	106	<0.01	<10	12	<10	4	>10000
4	E03301	>30	0.53	445	<5	<5	0.51	10	9	83	>10000	>10	<10	0.28	<1	123	0.06	6	1680	818	10	<20	46	<0.01	<10	12	<10	4	3966
5	E03302	25.4	0.29	730	<5	<5	0.24	<1	11	70	1180	>10	<10	0.26	<1	35	0.03	10	120	680	55	<20	30	<0.01	<10	9	<10	7	852
6	E03303	>30	0.56	840	<5	<5	1.02	196	5	40	2123	5.24	<10	0.17	<1	6	0.04	<1	220	>10000	80	<20	162	<0.01	<10	12	<10	2	>10000
7	E03304	11.4	1.09	435	<5	<5	1.08	44	22	56	350	4.98	<10	0.39	42	<1	0.12	18	200	5046	15	<20	116	<0.01	<10	33	<10	4	>10000
8	E03305	1.0	4.22	35	550	5	0.27	<1	27	241	67	4.46	<10	4.41	978	<1	0.06	87	730	64	<5	<20	34	0.08	<10	510	<10	4	671
9	E03306	8.4	1.63	295	10	<5	0.60	6	19	70	370	4.36	<10	1.33	241	2	0.10	31	380	924	15	<20	20	0.06	<10	48	<10	3	1933
10	E03307	12.7	0.48	150	20	<5	0.29	11	11	36	148	2.95	<10	0.31	20	3	0.03	13	190	1130	15	<20	34	<0.01	<10	15	<10	4	3228
11	E03308	25.9	0.26	175	<5	<5	0.32	414	7	20	359	1.91	<10	0.16	39	<1	0.02	<1	90	>10000	<5	<20	32	<0.01	<10	<1	<10	4	>10000
12	E03309	11.1	1.92	405	10	<5	0.33	212	23	133	4958	2.97	<10	2.04	425	<1	0.05	40	1040	>10000	<5	<20	36	0.08	<10	147	<10	4	>10000
13	E03310	24.9	0.84	120	20	<5	0.29	431	10	55	2933	1.60	<10	0.82	225	<1	0.03	3	430	>10000	<5	<20	34	0.02	<10	72	<10	4	>10000
14	E03311	4.4	2.50	185	5	<5	0.45	52	36	134	279	4.65	<10	2.61	542	<1	0.08	72	460	5172	<5	<20	26	0.10	<10	201	<10	4	>10000
15	E03312	<0.2	1.68	<5	155	<5	1.51	<1	20	73	34	3.19	<10	1.18	344	2	0.16	31	830	26	<5	<20	160	0.12	<10	168	<10	4	54
16	E03313	26.6	0.23	340	<5	<5	0.14	216	24	64	63	>10	<10	0.24	<1	<1	0.02	64	20	>10000	<5	<20	14	<0.01	<10	9	<10	8	>10000
17	E03314	28.6	0.13	705	<5	<5	0.24	116	14	77	305	>10	<10	0.27	<1	<1	0.02	49	<10	>10000	15	<20	18	<0.01	<10	9	<10	8	>10000
18	E03315	8.6	0.28	175	20	<5	0.13	11	5	40	224	2.34	<10	0.13	<1	<1	0.03	2	190	1562	20	<20	10	<0.01	<10	6	<10	6	2992
19	E03316	9.6	0.32	160	25	<5	0.15	<1	6	27	97	2.16	<10	0.19	5	<1	0.03	4	230	816	30	<20	10	<0.01	<10	6	<10	7	57
20	E03317	8.9	0.34	170	25	<5	0.17	<1	6	27	88	2.44	<10	0.20	<1	2	0.04	2	280	586	25	<20	10	<0.01	<10	3	<10	8	26
21	E03318	>30	0.09	1745	<5	<5	0.12	785	6	22	9322	4.43	<10	0.11	25	<1	0.02	<1	1430	>10000	895	<20	24	<0.01	<10	12	<10	2	>10000
22	E03319	6.0	0.36	130	15	<5	0.20	<1	7	27	98	3.34	<10	0.21	<1	<1	0.04	7	240	418	15	<20	14	<0.01	<10	6	<10	7	68
23	E03320	29.6	0.32	895	<5	<5	0.36	<1	11	89	683	>10	<10	0.34	<1	<1	0.04	21	50	882	60	<20	16	<0.01	<10	6	<10	6	171
24	E03321	28.1	0.47	320	5	<5	0.33	<1	9	30	284	4.40	<10	0.37	<1	3	0.04	10	280	2104	80	<20	18	<0.01	<10	6	<10	6	95
25	E03322	22.0	0.30	535	5	<5	0.38	109	7	25	921	3.40	<10	0.24	<1	<1	0.02	2	450	>10000	70	<20	32	<0.01	<10	3	<10	5	>10000

REDFERN RESOURCES LTD. ICP CERTIFICATE OF ANALYSIS AK 2003-466 ECO TECH LABORATORY LTD.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	E03323	15.2	0.22	630	<5	<5	0.26	<1	11	37	1161	8.64	<10	0.22	<1	7	0.02	7	460	1124	110	<20	10	<0.01	<10	3	<10	6	385
27	E03324	15.9	0.24	685	<5	<5	0.27	<1	11	39	1284	8.16	10	0.23	<1	7	0.02	9	470	138	105	<20	10	<0.01	<10	<1	<10	5	310
28	E03325	8.0	0.24	390	20	<5	0.41	20	11	30	892	3.23	10	0.19	<1	<1	0.02	7	300	234	110	<20	44	<0.01	<10	<1	<10	5	4412
29	E03326	3.6	0.28	215	25	<5	0.30	11	5	45	519	2.19	10	0.21	<1	1	0.02	2	340	22	60	<20	8	<0.01	<10	<1	<10	4	2510
30	E03327	0.7	0.50	110	30	<5	3.51	<1	9	58	226	4.55	40	0.66	69	2	0.02	14	410	46	20	<20	214	<0.01	<10	18	<10	7	84
31	E03328	6.9	2.77	15	70	<5	3.05	3	29	151	152	4.93	50	3.51	633	3	0.08	60	3340	76	<5	<20	88	0.04	<10	444	<10	12	179
32	E03329	2.2	0.66	110	35	<5	1.91	10	9	40	433	2.69	30	0.83	61	4	0.02	11	510	44	50	<20	136	<0.01	<10	12	<10	5	1802
33	E03330	1.7	1.43	80	35	<5	0.38	11	7	26	196	2.12	30	2.39	191	1	0.02	9	360	64	15	<20	18	<0.01	<10	9	<10	5	1950
34	E03331	0.6	1.89	50	35	<5	3.05	17	5	56	174	2.25	40	3.69	271	<1	0.01	14	430	78	<5	<20	324	<0.01	<10	6	<10	4	4058
35	E03332	0.2	0.95	45	100	5	>10	8	3	24	216	1.32	30	1.90	130	1	0.01	35	520	60	<5	<20	900	<0.01	<10	9	<10	5	1655
36	E03333	2.5	0.90	285	65	<5	2.58	26	11	37	4237	5.46	90	1.17	35	13	0.02	10	470	234	35	<20	220	<0.01	<10	<1	<10	6	3956
37	E03334	2.1	0.77	185	45	<5	0.29	48	12	34	7402	6.48	60	0.84	<1	19	0.02	<1	850	78	20	<20	10	<0.01	<10	<1	<10	5	>10000
38	E03335	4.3	0.83	440	10	<5	0.67	69	10	32	>10000	4.60	<10	0.87	74	10	0.01	<1	1390	190	30	<20	26	0.01	<10	<1	<10	6	>10000
39	E03336	1.0	0.60	60	20	<5	0.47	31	7	30	381	2.39	<10	0.51	41	<1	0.02	2	460	202	<5	<20	36	<0.01	<10	3	<10	4	8088
40	E03337	3.3	0.44	125	20	<5	0.30	29	5	63	598	1.71	<10	0.30	33	<1	0.01	<1	300	314	<5	<20	50	<0.01	<10	6	<10	3	8204
41	E03338	2.5	0.43	105	15	<5	0.34	29	5	54	485	1.87	<10	0.30	26	<1	0.01	2	320	258	<5	<20	38	<0.01	<10	6	<10	4	8105
42	E03339	2.1	0.28	70	25	<5	0.22	47	4	77	572	1.38	<10	0.15	18	4	<0.01	<1	150	1018	<5	<20	62	<0.01	<10	3	<10	2	>10000
43	E03340	2.5	0.92	50	40	<5	0.60	<1	20	59	2133	9.96	50	0.58	<1	5	0.05	16	570	158	10	<20	32	0.01	<10	15	<10	5	286
44	E03341	<0.2	0.32	10	50	5	0.20	<1	19	122	11	>10	<10	0.21	<1	5	0.02	1	110	10	10	<20	20	<0.01	<10	3	<10	3	23
45	E03342	<0.2	1.53	<5	100	10	1.46	<1	24	79	44	3.27	<10	1.14	292	3	0.13	29	1140	26	<5	<20	132	0.12	<10	36	<10	9	51
46	E03343	0.3	0.47	30	165	15	0.31	<1	28	98	6	>10	<10	0.38	<1	17	0.03	4	220	30	40	<20	42	<0.01	<10	3	<10	11	33
47	E03344	0.2	0.54	45	120	15	0.30	<1	19	74	12	9.16	<10	0.34	<1	18	0.04	2	210	22	25	<20	32	<0.01	<10	3	<10	7	33
48	E03345	0.4	0.68	130	165	25	0.41	2	20	71	14	>10	<10	0.47	<1	27	0.05	3	280	36	35	<20	46	<0.01	<10	<1	<10	10	28
49	E03346	0.2	0.50	<5	170	20	0.22	<1	24	45	5	9.95	<10	0.44	<1	33	0.03	<1	270	20	25	<20	46	<0.01	<10	<1	<10	11	26
50	E03347	<0.2	0.69	<5	155	25	0.41	<1	18	61	5	7.76	<10	0.51	<1	26	0.04	<1	540	32	25	<20	42	<0.01	<10	<1	<10	11	23
51	E03348	0.4	0.26	<5	120	10	0.28	<1	33	85	11	5.64	<10	0.23	3	22	<0.01	9	420	198	25	<20	20	<0.01	<10	12	<10	8	291
52	E03349	4.6	0.26	20	370	40	0.24	17	105	87	106	>10	<10	0.43	<1	76	<0.01	<1	250	700	45	<20	58	<0.01	<10	21	<10	14	5681
53	E03350	3.2	0.68	<5	285	45	0.52	5	75	61	88	>10	<10	0.47	<1	65	0.03	6	610	272	30	<20	50	<0.01	<10	39	<10	13	803
54	E03351	1.4	0.87	20	220	20	0.76	3	81	48	121	9.39	<10	0.49	4	39	0.04	21	1440	114	25	<20	36	<0.01	<10	54	<10	11	74
55	E03352	>30	1.22	520	60	<5	0.24	61	10	28	6328	3.76	<10	1.69	169	<1	0.03	8	520	1326	270	<20	26	<0.01	<10	12	<10	5	>10000
56	E03353	1.1	0.87	65	25	15	0.70	<1	62	47	102	8.92	<10	0.35	36	<1	0.05	22	960	74	10	<20	50	<0.01	<10	66	<10	6	60
57	E03354	1.0	0.85	85	15	10	0.61	<1	58	54	77	9.45	<10	0.36	34	<1	0.04	18	780	66	<5	<20	24	<0.01	<10	63	<10	4	53
58	E03355	1.4	0.86	150	20	10	0.54	<1	84	54	91	>10	<10	0.39	52	<1	0.03	39	280	82	5	<20	28	<0.01	<10	81	<10	4	61
59	E03356	0.3	1.77	45	25	<5	1.03	<1	59	44	46	6.09	<10	0.87	348	<1	0.06	22	930	58	<5	<20	36	0.04	<10	123	<10	5	83
60	E03357	0.2	2.18	30	35	15	0.98	<1	43	41	43	5.42	<10	1.40	639	<1	0.06	18	1050	54	5	<20	40	0.08	<10	108	<10	7	82
61	E03358	0.7	1.55	175	50	15	0.67	2	90	51	65	9.16	<10	1.10	405	<1	0.03	39	610	64	30	<20	26	0.05	<10	102	<10	6	66

REDFERN RESOURCES LTD. ICP CERTIFICATE OF ANALYSIS AK 2003-466 ECO TECH LABORATORY LTD.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC DATA:																													
Resplit:																													
1	E03298	0.7	2.31	10	315	<5	1.30	<1	6	61	131	2.03	40	1.43	201	4	0.14	10	500	154	10	<20	164	0.04	<10	<1	<10	5	374
36	E03333	2.2	0.86	310	40	<5	2.67	24	10	36	4300	5.69	60	1.09	32	13	0.02	13	480	162	45	<20	262	<0.01	<10	6	<10	4	4196
Repeat:																													
1	E03298	0.8	2.64	10	315	<5	1.22	<1	5	73	148	2.12	<10	1.29	249	2	0.21	12	350	92	<5	<20	258	0.04	<10	42	<10	3	323
10	E03307	12.9	0.46	155	15	<5	0.28	10	11	35	147	2.92	<10	0.30	19	3	0.03	13	190	1086	15	<20	36	<0.01	<10	12	<10	4	3077
19	E03316	9.7	0.31	140	30	<5	0.15	<1	6	26	96	2.23	<10	0.19	3	<1	0.03	3	240	834	30	<20	8	<0.01	<10	3	<10	8	53
36	E03333	2.5	0.85	345	50	<5	2.50	24	10	36	4201	5.57	60	1.07	31	11	0.02	10	440	214	45	<20	250	<0.01	<10	6	<10	3	4048
45	E03342	<0.2	1.43	<5	150	25	1.52	<1	27	78	43	2.96	150	1.30	226	24	0.11	23	1420	26	<5	<20	84	0.18	<10	<1	<10	19	51
Standard:																													
GEO '03		1.4	1.28	55	165	10	1.67	2	22	55	80	3.24	<10	0.97	502	3	0.02	29	790	22	<5	<20	48	0.08	<10	67	<10	11	69
GEO '03		1.4	1.33	55	155	10	1.69	2	22	58	84	3.50	<10	0.92	552	2	0.01	32	760	26	<5	<20	46	0.08	<10	68	<10	11	73

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/klh
df/466
XLS/03

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-501

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

5-Nov-03

ATTENTION: Bob Carmichael

No. of samples received: 38
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 30
Samples submitted by: NCA

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	E03359	<0.03	<0.001					
2	E03360	0.07	0.002					
3	E03361	0.47	0.014	17.2	0.50	0.14	1.30	3.32
4	E03362	0.24	0.007					
5	E03363	0.45	0.013					
6	E03364	0.20	0.006					
7	E03365	0.16	0.005					
8	E03366	<0.03	<0.001					
9	E03367	<0.03	<0.001					
10	E03368	0.26	0.008					
11	E03369	0.21	0.006					
12	E03370	0.30	0.009					
13	E03371	0.25	0.007					
14	E03372	0.09	0.003					
15	E03373	0.06	0.002					
16	E03374	0.06	0.002					
17	E03375	0.07	0.002					
18	E03376	0.08	0.002					
19	E03377	0.07	0.002					
20	E03378	0.10	0.003					
21	E03379	0.04	0.001					
22	E03380	0.05	0.001					
23	E03381	0.05	0.001					
24	E03382	0.10	0.003					
25	E03383	0.05	0.001					
26	E03384	0.05	0.001					
27	E03385	0.06	0.002					
28	E03386	0.03	0.001					
29	E03387	<0.03	<0.001					
30	E03388	0.28	0.008					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. AK 2003-501

5-Nov-03

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
31	E03389	0.24	0.007					
32	E03390	0.23	0.007					
33	E03391	2.12	0.062	318	9.27	1.48	10.8	13.8
34	E03392	0.44	0.013	30.6	0.89	1.03	1.56	3.59
35	E03393	0.39	0.011					
36	E03394	2.09	0.061	142	4.14	0.62	0.48	1.03
37	E03395	0.04	0.001					
38	E03396	0.22	0.006					
QC DATA:								
Repeat:								
1	E03359	<0.03	<0.001					
10	E03368	0.24	0.007					
19	E03377	0.09	0.003					
Resplit:								
1	E03359	<0.03	<0.001					
Standard:								
PM 163		1.69	0.049					
PM 163		1.66	0.048					

JJ/lh
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

CERTIFICATE OF ASSAY AK 2003-501

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

5-Nov-03

ATTENTION: Bob Carmichael

No. of samples received: 38
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 30
Samples submitted by: NCA

ET #.	Tag #	SG g/cm^3
3	E03361	3.12
34	E03392	3.39

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

4-Nov-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-501

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 38
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 30
Samples submitted by: NCA

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	E03359	0.2	1.42	5	155	<5	1.25	<1	5	38	85	1.94	20	1.35	355	<1	0.01	8	200	8	<5	<20	155	<0.01	<10	<1	<10	9	388
2	E03360	0.5	2.26	<5	170	<5	1.09	1	4	37	253	2.45	10	2.70	360	<1	<0.01	9	200	18	<5	<20	96	<0.01	<10	7	<10	4	1397
3	E03361	16.8	0.87	140	10	<5	1.19	111	5	22	1423	2.51	<10	1.41	162	<1	0.01	<1	160	>10000	290	<20	104	<0.01	<10	4	<10	3	>10000
4	E03362	5.3	0.31	55	5	<5	0.70	10	10	41	443	7.11	20	0.52	<1	2	<0.01	5	110	1689	25	<20	53	<0.01	<10	2	<10	<1	2689
5	E03363	9.2	0.26	115	10	<5	0.23	<1	11	60	3551	>10	20	0.30	<1	9	<0.01	9	180	24	60	<20	18	<0.01	<10	2	<10	<1	645
6	E03364	2.4	0.16	30	<5	<5	0.37	<1	10	95	139	>10	30	0.40	<1	4	<0.01	2	<10	144	25	<20	24	<0.01	<10	1	<10	<1	123
7	E03365	1.8	0.18	30	5	<5	0.25	<1	13	78	93	>10	30	0.27	<1	9	<0.01	2	30	48	10	<20	9	<0.01	<10	1	<10	<1	27
8	E03366	<0.2	0.43	<5	360	<5	3.78	<1	16	66	18	3.79	30	1.56	821	1	0.03	19	2190	12	<5	<20	260	<0.01	<10	22	<10	10	85
9	E03367	<0.2	2.22	<5	160	5	1.85	<1	20	93	27	3.34	10	1.45	405	2	0.22	32	870	26	<5	<20	104	0.10	<10	68	<10	14	49
10	E03368	0.2	0.32	25	10	<5	0.13	<1	10	53	55	2.39	<10	0.09	8	3	<0.01	3	20	36	<5	<20	56	<0.01	<10	2	<10	<1	54
11	E03369	2.6	0.18	25	10	<5	0.16	<1	7	62	38	2.81	<10	0.09	17	5	<0.01	4	<10	18	5	<20	18	<0.01	<10	<1	<10	<1	11
12	E03370	2.7	0.15	20	10	<5	0.11	<1	7	77	31	2.17	<10	0.06	16	5	<0.01	6	<10	12	5	<20	13	<0.01	<10	<1	<10	<1	9
13	E03371	6.6	0.25	75	<5	<5	0.22	<1	34	54	259	7.81	20	0.18	<1	5	<0.01	3	70	90	5	<20	17	<0.01	<10	2	<10	<1	19
14	E03372	0.6	0.38	15	35	<5	0.72	<1	3	72	69	1.47	<10	0.16	397	3	0.04	5	70	36	<5	<20	29	<0.01	<10	1	<10	5	32
15	E03373	0.2	0.22	15	45	<5	0.82	<1	<1	71	3	0.39	<10	0.04	459	3	0.04	3	40	30	<5	<20	26	<0.01	<10	<1	<10	6	35
16	E03374	0.2	0.28	10	240	<5	0.79	<1	<1	59	2	0.42	10	0.05	491	3	0.04	2	40	42	<5	<20	33	<0.01	<10	<1	<10	6	48
17	E03375	<0.2	0.24	<5	85	<5	0.58	<1	<1	72	5	0.45	<10	0.04	378	4	0.05	2	40	18	<5	<20	18	<0.01	<10	<1	<10	5	23
18	E03376	2.9	3.49	30	15	15	1.82	<1	29	131	56	7.58	20	4.44	851	13	0.02	50	330	421	<5	<20	46	0.03	<10	70	<10	3	114
19	E03377	2.9	1.34	10	10	5	1.91	<1	17	88	78	>10	40	2.65	463	2	<0.01	8	500	58	5	<20	52	<0.01	<10	6	<10	<1	77
20	E03378	0.7	0.81	10	15	10	1.86	<1	13	91	40	>10	40	1.82	318	<1	<0.01	8	340	18	<5	<20	41	<0.01	<10	3	<10	<1	95
21	E03379	0.2	0.74	10	10	<5	0.45	<1	9	86	84	8.94	20	1.02	32	11	<0.01	3	280	6	10	<20	19	<0.01	<10	2	<10	<1	28
22	E03380	0.4	0.79	15	10	<5	0.56	<1	5	92	105	3.01	<10	1.06	201	9	<0.01	5	210	10	10	<20	21	<0.01	<10	3	<10	2	28
23	E03381	0.3	2.80	15	25	<5	0.82	<1	10	86	22	>10	30	4.41	530	<1	<0.01	13	140	4	<5	<20	32	<0.01	<10	7	<10	<1	72
24	E03382	<0.2	1.75	<5	10	10	1.51	<1	11	89	14	>10	40	3.21	415	<1	<0.01	12	90	<2	<5	<20	13	<0.01	<10	5	<10	<1	42
25	E03383	<0.2	1.75	<5	10	5	0.54	<1	9	97	5	>10	40	3.12	190	<1	<0.01	5	<10	<2	<5	<20	49	<0.01	<10	5	<10	<1	43

DEC 11 2003

Eco Tech Laboratory Ltd.

ANALYTICAL ENVIRONMENTAL GEOCHEMISTRY TESTING

CERTIFICATE OF ASSAY AK 2003-588

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

2-Dec-03

ATTENTION: Bob Carmichael

No. of samples received: 45
Sample type: Core
Project #: Tulsequah Chief
Shipment #: Not Given
Samples submitted by: S.C.

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	E03455	0.09	0.003					
2	E03456	0.32	0.009	30.3	0.884	0.06	0.40	0.88
3	E03457	0.24	0.007					
4	E03458	0.33	0.010	35.1	1.024	0.26	0.44	1.32
5	E03459	0.09	0.003					
6	E03460	0.15	0.004					
7	E03461	0.34	0.010					
8	E03462	0.53	0.015					
9	E03463	0.79	0.023					
10	E03464	1.75	0.051					
11	E03465	0.68	0.020					
12	E03466	0.17	0.005					
13	E03467	<0.03	<0.001					
14	E03468	0.11	0.003					
15	E03469	0.07	0.002					
16	E03470	0.05	0.001					
17	E03471	0.22	0.006					
18	E03472	0.69	0.020					
19	E03473	<0.03	<0.001					
20	E03474	<0.03	<0.001					
21	E03475	<0.03	<0.001					
22	E03476	0.06	0.002					
23	E03477	0.08	0.002					
24	E03478	0.06	0.002					
25	E03479	0.05	0.001					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

REDFERN RESOURCES LTD. AK3-588 2-Dec-03

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
26	E03480	0.05	0.001					
27	E03481	<0.03	<0.001					
28	E03482	<0.03	<0.001					
29	E03483	0.14	0.004					
30	E03484	0.18	0.005					
31	E03485	0.04	0.001					
32	E03486	<0.03	<0.001					
33	E03487	0.03	0.001					
34	E03488	<0.03	<0.001					
35	E03489	<0.03	<0.001					
36	E03490	0.05	0.001					
37	E03491	2.12	0.062	139	4.05	0.63	0.49	1.01
38	E03492	0.11	0.003					
39	E03493	0.03	0.001					
40	E03494	2.06	0.060	309	9.01	1.50	10.9	14.8
41	E03495	0.05	0.001					
42	E03496	<0.03	<0.001					
43	E03497	0.08	0.002					
44	E03498	<0.03	<0.001					
45	E03499	0.06	0.002					
QC DATA:								
Repeat:								
1	E03455	0.09	0.003					
4	E03458	0.34	0.010					
7	E03461	0.31	0.009					
8	E03462	0.36	0.010					
9	E03463	0.71	0.021					
10	E03464	1.68	0.049					
11	E03465	0.64	0.019					
19	E03473	<0.03	<0.001					
36	E03490	0.05	0.001					
Resplit:								
1	E03455	0.06	0.002					
36	E03490	0.05	0.001					
Standard:								
PM163		1.60	0.047					
PM163		1.67	0.049					
CU106				134	3.91	1.43		
PB106				57.1	1.67	0.64	0.53	0.86

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

CERTIFICATE OF ASSAY AK 2003-588

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

2-Dec-03

ATTENTION: Bob Carmichael

No. of samples received: 45
Sample type: Core
Project #: Tulsequah Chief
Shipment #: Not Given
Samples submitted by: S.C.

ET #.	Tag #	SG g/cm^3
2	E03456	3.24
4	E03458	2.74

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

28-Nov-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-588

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 45
Sample type: Core
Project #: Tulsequah Chief
Shipment #: Not Given
Samples submitted by: S.C.

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	E03455	2.5	0.98	95	15	<5	0.82	<1	8	34	128	4.24	<10	0.85	272	<1	0.03	6	190	166	10	<20	14	0.04	<10	3	<10	4	356
2	E03456	>30	1.19	180	<5	<5	0.82	14	13	67	599	9.29	10	0.74	218	<1	0.04	11	910	3418	105	<20	7	0.10	<10	7	<10	6	8309
3	E03457	29.9	0.68	120	15	<5	0.46	2	10	63	1878	3.61	<10	0.50	117	4	0.04	14	470	456	320	<20	17	0.07	10	5	<10	4	652
4	E03458	>30	0.84	95	5	<5	0.40	44	12	44	2498	5.78	<10	0.58	101	4	0.03	14	590	4466	150	<20	2	0.09	10	4	<10	4	>10000
5	E03459	3.6	0.56	65	25	<5	0.70	12	4	58	660	2.94	<10	0.34	135	5	0.02	6	360	370	65	<20	6	0.04	<10	3	<10	3	3193
6	E03460	1.1	0.66	75	10	<5	0.34	<1	7	73	252	4.84	<10	0.51	39	8	0.04	16	260	78	45	<20	5	0.05	<10	3	<10	3	261
7	E03461	1.4	1.00	150	10	<5	0.41	<1	8	69	183	6.34	10	0.65	67	14	0.07	9	290	78	30	<20	7	0.07	10	3	<10	3	203
8	E03462	11.9	1.03	125	5	<5	0.65	6	9	75	2416	8.21	20	0.76	63	5	0.07	7	400	222	145	<20	4	0.11	<10	3	<10	6	1481
9	E03463	7.6	0.60	100	15	<5	1.00	3	7	57	645	5.90	10	0.40	64	4	0.03	5	310	318	75	<20	6	0.06	<10	2	<10	6	791
10	E03464	17.1	0.52	80	10	<5	0.48	9	7	77	418	5.61	10	0.41	21	2	0.04	4	260	1036	55	<20	2	0.06	<10	2	<10	3	2316
11	E03465	8.7	0.65	60	10	<5	0.57	4	8	59	720	5.25	<10	0.53	75	3	0.03	5	350	674	20	<20	<1	0.05	<10	2	<10	3	1090
12	E03466	3.9	0.98	50	20	<5	0.74	<1	6	61	487	4.08	<10	0.78	161	1	0.03	5	390	44	<5	<20	7	0.05	<10	2	<10	4	76
13	E03467	<0.2	1.94	<5	150	5	1.35	<1	22	78	27	3.02	10	1.08	297	1	0.24	28	770	34	<5	<20	132	0.15	<10	71	<10	7	44
14	E03468	3.2	0.93	30	25	<5	0.63	<1	5	75	210	3.42	<10	0.72	151	<1	0.04	7	320	44	<5	<20	10	0.04	<10	2	<10	3	94
15	E03469	6.1	1.31	20	35	<5	1.69	2	7	46	278	3.13	<10	1.06	298	3	0.05	11	490	158	10	<20	34	0.04	<10	6	<10	5	347
16	E03470	4.5	1.24	15	30	<5	1.27	1	8	45	228	3.25	<10	0.99	233	2	0.04	9	540	124	<5	<20	24	0.04	<10	5	<10	5	228
17	E03471	23.5	0.72	25	10	<5	1.22	18	7	91	558	4.07	<10	0.51	177	4	0.05	14	340	1622	30	<20	15	0.05	<10	8	<10	3	3194
18	E03472	18.6	0.52	30	15	<5	1.03	9	8	60	1483	4.22	<10	0.41	108	6	0.03	9	200	166	75	<20	16	0.06	<10	2	<10	3	1480
19	E03473	0.2	0.32	<5	30	<5	0.91	<1	5	78	119	2.70	<10	0.37	125	2	0.02	6	370	10	10	<20	24	0.03	<10	<1	<10	4	32
20	E03474	<0.2	0.52	<5	35	<5	0.79	<1	3	78	743	2.09	<10	0.43	140	4	0.02	5	330	10	5	<20	10	0.03	<10	1	<10	3	29
21	E03475	<0.2	0.62	<5	40	<5	0.62	2	5	73	452	1.77	<10	0.40	106	<1	0.03	7	340	10	<5	<20	6	0.02	<10	2	<10	2	406
22	E03476	1.6	0.28	25	20	<5	0.32	1	5	86	1558	2.88	<10	0.14	25	5	0.02	6	110	20	5	20	4	0.04	<10	<1	<10	<1	300
23	E03477	1.6	0.24	95	10	<5	0.12	<1	6	73	676	3.51	<10	0.08	<1	3	0.02	4	170	14	10	<20	2	0.04	<10	<1	<10	1	80
24	E03478	1.0	0.37	60	10	<5	0.27	6	7	72	882	4.38	<10	0.28	8	5	0.02	5	180	12	<5	<20	6	0.05	<10	1	<10	1	1490
25	E03479	0.3	0.48	60	15	<5	0.67	<1	9	66	152	3.35	<10	0.48	81	3	0.02	9	310	14	5	<20	11	0.03	<10	2	<10	2	69

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-594

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

4-Dec-03

ATTENTION: Bob Carmichael

No. of samples received: 27
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 32
Samples submitted by: S.C.

ET #.	Tag #	SG g/cm³
2	E03429	3.54
8	E03435	3.39
9	E03436	2.86
10	E03437	2.83
11	E03438	2.84
12	E03439	3.14
13	E03440	2.95
14	E03441	2.79
16	E03443	2.98
17	E03444	3.10
18	E03445	3.20
19	E03446	3.62
20	E03447	2.76
21	E03448	3.42
22	E03449	3.31

JJ/kk
XLS/03

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2003-594

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

4-Dec-03

ATTENTION: Bob Carmichael

No. of samples received: 27
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 32
Samples submitted by: S.C.

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	E03428	0.17	0.005					
2	E03429	5.67	0.165	3069	89.50	2.60	4.13	13.8
3	E03430	0.37	0.011					
4	E03431	<0.03	<0.001					
5	E03432	0.69	0.020					
6	E03433	0.22	0.006					
7	E03434	0.83	0.024					
8	E03435	0.43	0.013	5.6	0.16	0.17	0.08	6.00
9	E03436	0.56	0.016	6.4	0.19	0.25	0.06	0.75
10	E03437	0.13	0.004	1.9	0.06	0.10	0.02	0.66
11	E03438	0.16	0.005	3.3	0.10	0.19	0.02	1.25
12	E03439	0.75	0.022	145	4.23	1.03	0.13	8.90
13	E03440	0.18	0.005	18.1	0.53	0.44	0.05	1.33
14	E03441	0.07	0.002	0.4	0.01	0.01	0.01	0.05
15	E03442	<0.03	<0.001					
16	E03443	0.43	0.013	3.2	0.09	0.15	0.02	0.07
17	E03444	0.62	0.018	6.9	0.20	0.64	0.27	1.80
18	E03445	0.52	0.015	5.4	0.16	0.82	0.03	6.20
19	E03446	1.08	0.031	20.2	0.59	0.46	0.8	4.35
20	E03447	<0.03	<0.001	0.2	0.01	0.02	0.01	0.48
21	E03448	0.28	0.008	12.6	0.37	0.61	1.65	10.3
22	E03449	0.57	0.017	12.9	0.38	0.37	0.58	6.20
23	E03450	0.48	0.014					
24	E03451	<0.03	<0.001					

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

28-Nov-03

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2003-594

REDFERN RESOURCES LTD.
760-777 Hornby Street
Vancouver, BC
V6Z 1S4

ATTENTION: Bob Carmichael

No. of samples received: 27
Sample type: Core
Project #: Tulsequah Chief
Shipment #: 32
Samples submitted by: S.C.

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	E03428	2.1	2.52	10	415	<5	1.25	<1	10	80	362	2.09	<10	1.36	234	5	0.18	25	410	102	45	<20	74	0.25	<10	9	<10	5	679
2	E03429	>30	1.02	<5	40	<5	0.61	493	22	58	>10000	3.18	<10	0.36	132	2958	0.05	404	770	>10000	<5	<20	55	0.30	<10	5	<10	2	>10000
3	E03430	7.9	1.79	30	45	<5	0.57	18	12	39	1544	4.27	<10	1.26	198	10	0.08	11	360	948	10	<20	25	0.10	<10	6	<10	5	3816
4	E03431	3.0	3.96	10	855	10	1.60	<1	31	165	125	4.95	10	3.04	474	13	0.25	52	820	138	5	<20	82	0.67	<10	142	<10	5	431
5	E03432	6.6	2.03	30	90	<5	1.28	3	17	56	2158	2.37	<10	0.80	225	7	0.15	21	210	370	20	<20	66	0.20	<10	32	<10	2	822
6	E03433	2.9	4.47	10	755	<5	0.77	1	37	203	1182	5.59	10	3.70	633	8	0.16	72	720	254	10	<20	60	0.55	<10	103	<10	6	1573
7	E03434	5.9	1.19	5	70	<5	0.68	18	8	24	2110	1.50	<10	0.27	71	6	0.11	7	130	376	15	<20	83	0.09	<10	6	<10	2	4777
8	E03435	5.8	0.76	<5	35	<5	0.59	223	11	34	1684	1.74	<10	0.50	141	<1	0.04	4	120	786	<5	<20	58	0.13	<10	14	<10	<1	>10000
9	E03436	6.6	1.20	35	35	<5	0.63	29	18	39	2520	3.78	<10	0.67	129	<1	0.07	18	250	670	55	<20	22	0.09	<10	14	<10	3	7113
10	E03437	2.1	1.04	15	30	<5	0.57	32	28	24	897	3.33	<10	0.41	39	4	0.11	37	90	220	<5	<20	24	0.08	<10	7	<10	2	6247
11	E03438	3.1	1.12	15	25	<5	0.65	72	20	30	1884	3.44	<10	0.46	51	<1	0.12	27	150	244	<5	<20	28	0.07	<10	8	<10	2	>10000
12	E03439	>30	0.56	1030	45	<5	0.44	390	9	25	6166	2.59	<10	0.33	40	<1	0.03	2	260	1114	610	<20	38	0.09	<10	3	<10	2	>10000
13	E03440	17.5	0.57	165	20	<5	0.37	68	7	21	4248	3.05	<10	0.29	14	2	0.04	6	290	442	95	<20	37	0.08	<10	4	<10	3	>10000
14	E03441	0.4	4.91	15	225	<5	1.47	<1	36	224	129	5.33	10	3.98	643	8	0.25	72	720	110	<5	<20	78	0.46	<10	174	<10	6	509
15	E03442	<0.2	2.16	5	225	5	1.74	<1	33	81	24	3.59	10	1.41	383	14	0.20	32	920	40	<5	<20	112	0.67	<10	66	<10	8	61
16	E03443	3.4	0.83	30	15	<5	0.41	3	14	74	1393	7.21	10	0.59	14	7	0.05	36	190	144	<5	<20	29	0.17	<10	13	<10	2	670
17	E03444	6.8	1.54	95	30	<5	0.60	68	9	51	5553	7.57	10	1.42	136	17	0.05	7	300	2264	10	<20	27	0.18	<10	11	<10	2	>10000
18	E03445	5.6	3.50	145	40	<5	0.57	274	7	50	6898	6.71	10	4.19	517	15	0.05	3	820	294	<5	<20	40	0.21	10	33	<10	2	>10000
19	E03446	19.6	0.77	1005	20	<5	0.63	174	10	79	3802	>10	30	0.65	<1	5	0.04	<1	650	7404	175	<20	16	0.15	<10	6	<10	3	>10000
20	E03447	0.2	3.51	25	85	<5	0.39	20	37	259	182	5.07	10	4.05	673	3	0.07	87	630	150	<5	<20	47	0.24	<10	156	<10	6	4185

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
21	E03448	12.7	0.92	10	25	<5	0.96	545	10	55	5748	6.44	10	0.76	84	23	0.04	2	260	>10000	<5	<20	54	0.22	<10	13	<10	2	>10000
22	E03449	13.0	0.73	185	20	<5	1.28	284	8	53	3491	9.02	20	0.75	28	29	0.03	<1	190	5546	200	<20	35	0.12	<10	3	<10	1	>10000
23	E03450	3.1	0.56	70	20	<5	0.83	3	6	32	291	4.06	<10	0.31	20	1	0.05	5	460	234	70	<20	20	0.04	<10	<1	<10	5	719
24	E03451	0.3	0.69	<5	10	<5	0.47	<1	10	58	139	8.25	20	0.38	<1	1	0.06	5	480	14	5	<20	17	0.07	<10	<1	<10	5	53
25	E03452	>30	1.32	585	20	<5	0.21	47	7	26	6287	3.36	<10	1.52	191	<1	0.05	9	520	4898	275	<20	17	0.09	<10	3	<10	2	>10000
26	E03453	0.7	0.72	55	10	<5	0.43	<1	18	74	123	5.69	10	0.38	<1	2	0.07	16	340	34	<5	<20	12	0.06	<10	3	<10	4	88
27	E03454	0.6	0.61	30	35	5	0.49	2	9	58	34	2.79	<10	0.32	56	3	0.06	9	300	48	5	<20	10	0.03	<10	3	<10	5	106
QC DATA:																													
Resplit:																													
1	E03428	2.6	2.53	15	375	<5	1.32	<1	9	77	338	2.09	<10	1.33	229	2	0.18	27	420	112	55	<20	74	0.14	<10	11	<10	4	730
Repeat:																													
1	E03428	2.0	2.46	15	395	<5	1.23	<1	11	80	361	2.08	<10	1.34	232	9	0.18	26	410	104	45	<20	70	0.44	<10	8	<10	5	670
10	E03437	2.3	1.01	20	30	<5	0.56	32	28	24	926	3.35	<10	0.41	37	4	0.11	37	100	220	<5	<20	23	0.06	<10	7	<10	2	6319
19	E03446	19.4	0.74	985	<5	<5	0.63	177	9	77	3743	>10	20	0.63	<1	3	0.04	1	630	7458	170	<20	15	0.15	<10	6	<10	2	>10000
Standard:																													
GEO '03		1.6	1.56	60	140	5	1.63	<1	20	57	86	3.43	10	0.93	618	3	0.03	31	720	24	5	<20	48	0.23	<10	66	<10	9	77

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
df/588
XLS/03

15500.0 N
10000.0 E
15400.0 N
10000.0 E
15300.0 N
10400.0 E
15000.0 N

700.0 m asl
600.0 m asl
500.0 m asl
400.0 m asl
300.0 m asl
200.0 m asl
100.0 m asl
0.0 m asl
-100.0 m asl
-200.0 m asl
-300.0 m asl
-400.0 m asl
-500.0 m asl
-600.0 m asl
-700.0 m asl
-800.0 m asl

LEGEND

LITHOLOGY : ROCKTYPE (LEFT)
NESTED : ROCKTYPE (RIGHT)

DI
VI
SED
QFP
FELSK
EXT
ZNF
CLF
CHT
FEVL
MAGX
ANFR
AND
AHM
AGGL
QPPY
QRDS
QRSU
QRSC
CLM
MDDD
F
FALT
SSH
QSP
BIN
PYF
SMS
BLT
BFL
BFLS
BLTS
CHF
BAT
BINI
CHL
BAU
BAUI
QZF
BFLI
PYWR
BDY
BAUS
BFL
FLZN
DSX
BAG
BHY
SMPY
STWK
DBF
FAUL
RDER
BMYS
RFX
BAHY
BFXS
RAT
RLAT
RFLI
RFX
RLT
RALT
RYU
QZSX
RFL
RDF
AMOX
FLSX
MSSX
BFX
RHYL

ASSAYS : ZNPPM (LEFT)

0.0000 - 50.0000
50.0000 - 100.0000
100.0000 - 200.0000
200.0000 - 500.0000
500.0000 - 1000.0000
1000.0000 - 1000000.0000

ASSAYS : CUPPM (RIGHT)

0.0000 - 50.0000
50.0000 - 100.0000
100.0000 - 200.0000
200.0000 - 500.0000
500.0000 - 1000.0000
1000.0000 - 1000000.0000

ASSAYS : ZNPPM (LEFT)

Upper Bound 10000.0000
Lower Bound 1.0000

ASSAYS : CUPPM (RIGHT)

Upper Bound 10000.0000
Lower Bound 1.0000

XXX
HOLE-ID

POLYGON LEGEND

TARGET OUTLINE — Year

HATCH PATTERNS - 'ROCKCODE'

BFLS
RHYL
MSSX
BIN
QSP
STWK

FILL HATCH COLOURS - 'ROCKCODE'

'DI'
'VI'
'SED'
'QFP'
'FELSK'
'EXT'
'ZNF'
'CLF'
'CHT'
'FEVL'
'MAGX'
'ANFR'
'AND'
'AHM'
'AGGL'
'QPPY'
'QRDS'
'QRSU'
'QRSC'
'CLM'
'MDDD'
'F'
'FALT'
'SSH'
'QSP'
'BIN'
'PYF'
'SMS'
'BLT'
'BFL'
'BFLS'
'BLTS'
'CHF'
'BAT'
'BINI'
'CHL'
'BAU'
'BAUI'
'QZF'
'BFLI'
'PYWR'
'BDY'
'BAUS'
'BFL'
'FLZN'
'DSX'
'BAG'
'BHY'
'SMPY'
'STWK'
'DBF'
'FAUL'
'RDER'
'BMYS'
'RFX'
'BAHY'
'BFXS'
'RAT'
'RLAT'
'RFLI'
'RFX'
'RLT'
'RALT'
'RYU'
'QZSX'
'RFL'
'RDF'
'AMOX'
'FLSX'
'MSSX'
'BFX'
'RHYL'

UNITS : METRES DATE: 04/03/29 TIME: 17:07:26
DRAWN BY : RGC

Tulsequah Chief Property
Section Azimuth 270

M1

27365

3 of 3

Software by Geovia Software International

15500.0 N
10800.0 E
15400.0 N
10600.0 E
15300.0 N
10400.0 E
15000.0 N

700.0 m asl
600.0 m asl
500.0 m asl
400.0 m asl
300.0 m asl
200.0 m asl
100.0 m asl
0.0 m asl
-100.0 m asl
-200.0 m asl
-300.0 m asl
-400.0 m asl
-500.0 m asl
-600.0 m asl
-700.0 m asl
-800.0 m asl

LEGEND

LITHOLOGY : ROCKTYPE (LEFT)
NESTED : ROCKTYPE (RIGHT)

HOLE-ID
XXX

- DH
- VH
- SRD
- QFP
- FEDK
- EXT
- ZNF
- CLF
- CHT
- FEVL
- MAGX
- ANFR
- AND
- ANHM
- AGGL
- ORPY
- ORDS
- ORSU
- ORSC
- DUM
- NODD
- F
- FALT
- SSH
- QSP
- BIN
- PYF
- SMS
- BLT
- BFL
- BFLS
- BLTS
- CHF
- BAT
- BINI
- CHL
- BAU
- BAUI
- DYF
- BFLI
- PYAR
- BDY
- BAUS
- BFL
- FL2N
- DSX
- BAG
- BMY
- SMPY
- STWK
- DIF
- FAUL
- RSER
- BMYS
- RFX
- BAMY
- BFXS
- RAT
- RLAT
- RFLI
- RFX
- RLT
- RALT
- RYU
- QZBX
- RFL
- RDF
- ANDK
- FLBX
- MSSX
- BFX
- RHYL

ASSAYS : ZNPPM (LEFT)

- 0.0000 - 50.0000
- 50.0000 - 100.0000
- 100.0000 - 200.0000
- 200.0000 - 500.0000
- 500.0000 - 1000.0000
- 1000.0000 - 1000000.0000

ASSAYS : CUPPM (RIGHT)

- 0.0000 - 50.0000
- 50.0000 - 100.0000
- 100.0000 - 200.0000
- 200.0000 - 500.0000
- 500.0000 - 1000.0000
- 1000.0000 - 1000000.0000

ASSAYS : ZNPPM (LEFT)

Upper Bound 10000.0000
Lower Bound 1.0000

ASSAYS : CUPPM (RIGHT)

Upper Bound 10000.0000
Lower Bound 1.0000

POLYGON LEGEND

TARGET OUTLINE

HATCH PATTERNS - 'ROCKCODE'

- BFLS
- RHYL
- MSSX
- BIN
- QSP
- STWK

FILL HATCH COLOURS - 'ROCKCODE'

- 'DH'
- 'VH'
- 'SRD'
- 'QFP'
- 'FEDK'
- 'EXT'
- 'ZNF'
- 'CLF'
- 'CHT'
- 'FEVL'
- 'MAGX'
- 'ANFR'
- 'AND'
- 'ANHM'
- 'AGGL'
- 'ORPY'
- 'ORDS'
- 'ORSU'
- 'ORSC'
- 'DUM'
- 'NODD'
- 'F'
- 'FALT'
- 'SSH'
- 'QSP'
- 'BIN'
- 'PYF'
- 'SMS'
- 'BLT'
- 'BFL'
- 'BFLS'
- 'BLTS'
- 'CHF'
- 'BAT'
- 'BINI'
- 'CHL'
- 'BAU'
- 'BAUI'
- 'DYF'
- 'BFLI'
- 'PYAR'
- 'BDY'
- 'BAUS'
- 'BFL'
- 'FL2N'
- 'DSX'
- 'BAG'
- 'BMY'
- 'SMPY'
- 'STWK'
- 'DIF'
- 'FAUL'
- 'RSER'
- 'BMYS'
- 'RFX'
- 'BAMY'
- 'BFXS'
- 'RAT'
- 'RLAT'
- 'RFLI'
- 'RFX'
- 'RLT'
- 'RALT'
- 'RYU'
- 'QZBX'
- 'RFL'
- 'RDF'
- 'ANDK'
- 'FLBX'
- 'MSSX'
- 'BFX'
- 'RHYL'

UNITS : METRES DATE: 04/03/29 TIME: 14:52:53
DRAWN BY : RGC


Tulsequah Chief Property
Section Azimuth 257

M2

Software by Geosoft Software International

15000.0 N
10000.0 E
15400.0 N
10000.0 E
15200.0 N
10400.0 E
15000.0 N

700.0 m asl
600.0 m asl
500.0 m asl
400.0 m asl
300.0 m asl
200.0 m asl
100.0 m asl
0.0 m asl
-100.0 m asl
-200.0 m asl
-300.0 m asl
-400.0 m asl
-500.0 m asl
-600.0 m asl
-700.0 m asl
-800.0 m asl



LEGEND

LITHOLOGY : ROCKTYPE (LEFT)
MESTED : ROCKTYPE (RIGHT)

DI
VH
SRD
QFP
FEDK
EXT
ZNF
CLF
CHT
FENL
MAGX
ANFR
AND
ANHM
AGGL
QPPY
QPDS
QPDU
QPDC
CLM
MCCO
IF
FALT
SSH
QSP
BIN
PYF
SMS
RLT
BFL
BFLS
BLTS
CHF
BAT
BINI
CHL
BAU
BAUI
CHF
BFLI
PYWR
BIDY
BAUS
BFL
FLZN
DSX
BAG
BHY
SMPY
STWK
DBF
FAUL
RSER
BHYS
RFX
BAHY
BFXS
RAT
RLAT
RFLI
RFX
RLT
RALT
RYU
QZBX
RFL
RDF
ANDK
FLDX
MSSX
RFX
RHYL

ASSAYS : ZNPPM (LEFT)

0.0000 - 50.0000
50.0000 - 100.0000
100.0000 - 200.0000
200.0000 - 500.0000
500.0000 - 1000.0000
1000.0000 - 1000000.0000

ASSAYS : CUPPM (RIGHT)

0.0000 - 50.0000
50.0000 - 100.0000
100.0000 - 200.0000
200.0000 - 500.0000
500.0000 - 1000.0000
1000.0000 - 1000000.0000

ASSAYS : ZNPPM (LEFT)

Upper Bound 10000.0000
Lower Bound 1.0000

ASSAYS : CUPPM (RIGHT)

Upper Bound 10000.0000
Lower Bound 1.0000

XXX
HOLE-ID

POLYGON LEGEND

TARGET OUTLINE

HATCH PATTERNS - 'ROCKCODE'

BFLS
RHYL
MSSX
BIN
QSP
STWK

FILL HATCH COLOURS - 'ROCKCODE'

'DI'
'VH'
'SRD'
'QFP'
'FEDK'
'EXT'
'ZNF'
'CLF'
'CHT'
'FENL'
'MAGX'
'ANFR'
'AND'
'ANHM'
'AGGL'
'QPPY'
'QPDS'
'QPDU'
'QPDC'
'CLM'
'MCCO'
'IF'
'FALT'
'SSH'
'QSP'
'BIN'
'PYF'
'SMS'
'RLT'
'BFL'
'BFLS'
'BLTS'
'CHF'
'BAT'
'BINI'
'CHL'
'BAU'
'BAUI'
'CHF'
'BFLI'
'PYWR'
'BIDY'
'BAUS'
'BFL'
'FLZN'
'DSX'
'BAG'
'BHY'
'SMPY'
'STWK'
'DBF'
'FAUL'
'RSER'
'BHYS'
'RFX'
'BAHY'
'BFXS'
'RAT'
'RLAT'
'RFLI'
'RFX'
'RLT'
'RALT'
'RYU'
'QZBX'
'RFL'
'RDF'
'ANDK'
'FLDX'
'MSSX'
'RFX'
'RHYL'

UNITS : METRES DATE: 04/03/29 TIME: 14:51:04
DRAWN BY : RGC


Tulsequah Chief Property
Section Azimuth 255

M3

27,255

GEOLOGICAL SURVEY BRANCH
ASSESSMENT REPORT

Software by Geosoft Software International



LEGEND

LITHOLOGY : ROCKTYPE (LEFT)
MESTED : ROCKTYPE (RIGHT)

DH
VH
SRD
QFP
FEDK
EXT
ZNF
CLF
CHT
FEVL
MNCK
ANFR
AND
ANHM
AGGL
CRPY
CRDS
CRSU
CRSC
DUM
NODO
F
FALT
SDH
QSP
BIN
PYF
SMS
BLT
BFL
BFLS
BLTS
CHF
BAT
BINI
CHL
BAU
BAUI
GYF
BFLI
PYWR
BDY
BAUS
BFL
FLZN
DDK
BAG
BMY
SMPY
STWK
DBF
FAUL
RBER
BMYS
RFX
BAYY
BFXS
RAT
RLAT
RFLI
RFX
RLT
RALT
RYU
QZSX
RFL
RDF
ANDK
FLSX
MSSX
BFX
RHYL

ASSAYS : ZNPPM (LEFT)

0.0000 - 50.0000
50.0000 - 100.0000
100.0000 - 200.0000
200.0000 - 500.0000
500.0000 - 1000.0000
1000.0000 - 1000000.0000

ASSAYS : CUPPM (RIGHT)

0.0000 - 50.0000
50.0000 - 100.0000
100.0000 - 200.0000
200.0000 - 500.0000
500.0000 - 1000.0000
1000.0000 - 1000000.0000

ASSAYS : ZNPPM (LEFT)

Upper Bound 10000.0000
Lower Bound 1.0000

ASSAYS : CUPPM (RIGHT)

Upper Bound 10000.0000
Lower Bound 1.0000

XXX
HOLE-ID

POLYGON LEGEND

TARGET OUTLINE

HATCH PATTERNS - 'ROCKCODE'

BFLS
RHYL
MSSX
BIN
QSP
STWK

FILL HATCH COLOURS - 'ROCKCODE'


'DH'
'VH'
'SRD'
'QFP'
'FEDK'
'EXT'
'ZNF'
'CLF'
'CHT'
'FEVL'
'MNCK'
'ANFR'
'AND'
'ANHM'
'AGGL'
'CRPY'
'CRDS'
'CRSU'
'CRSC'
'DUM'
'NODO'
'F'
'FALT'
'SDH'
'QSP'
'BIN'
'PYF'
'SMS'
'BLT'
'BFL'
'BFLS'
'BLTS'
'CHF'
'BAT'
'BINI'
'CHL'
'BAU'
'BAUI'
'GYF'
'BFLI'
'PYWR'
'BDY'
'BAUS'
'BFL'
'FLZN'
'DDK'
'BAG'
'BMY'
'SMPY'
'STWK'
'DBF'
'FAUL'
'RBER'
'BMYS'
'RFX'
'BAYY'
'BFXS'
'RAT'
'RLAT'
'RFLI'
'RFX'
'RLT'
'RALT'
'RYU'
'QZSX'
'RFL'
'RDF'
'ANDK'
'FLSX'
'MSSX'
'BFX'
'RHYL'

UNITS : METRES DATE: 04/03/29 TIME: 14:34:59
DRAWN BY : RGC

Tulsequah Chief Property
Section Azimuth 242

MH

Software by Geosoft Software International



LEGEND

LITHOLOGY : ROCKTYPE (LEFT)
HOSTED : ROCKTYPE (RIGHT)

DI
VH
SMD
QFP
FEDK
EXT
ZNF
CLF
CHT
FEML
MNCK
ANFR
AND
ANHM
AGGL
CRPY
CROS
CROU
CRSC
DUM
NODO
F
FALT
SSH
QSP
BIN
PYF
SMS
BLT
BFL
BFLS
BLTS
CHF
BAT
BINI
CYL
BAU
BAUI
CYF
BFLI
PYAR
BOY
BALS
BFL
FLZN
DSK
BAG
BMY
SMPY
STWK
DBF
FAUL
RBER
BMYS
RFX
BAMY
BFXS
RAT
RLAT
RFLI
RFX
RLT
RALT
RYU
GZSX
RFL
REF
ANOM
FLSX
MSSX
BFX
RAYL

ASSAYS : ZNPPM (LEFT)

	0.0000 - 50.0000
	50.0000 - 100.0000
	100.0000 - 200.0000
	200.0000 - 500.0000
	500.0000 - 1000.0000
	1000.0000 - 10000000.0000

ASSAYS : CUPPM (RIGHT)

	0.0000 - 50.0000
	50.0000 - 100.0000
	100.0000 - 200.0000
	200.0000 - 500.0000
	500.0000 - 1000.0000
	1000.0000 - 10000000.0000

ASSAYS : ZNPPM (LEFT)
Upper Bound 10000.0000
Lower Bound 1.0000

ASSAYS : CUPPM (RIGHT)
Upper Bound 10000.0000
Lower Bound 1.0000

XXX
HOLE-ID

POLYGON LEGEND

TARGET OUTLINE

HATCH PATTERNS - 'ROCKCODE'

BFLS
RAYL
MSSX
BIN
QSP
STWK

FILL HATCH COLOURS - 'ROCKCODE'

'DI'
'VH'
'SMD'
'QFP'
'FEDK'
'EXT'
'ZNF'
'CLF'
'CHT'
'FEML'
'MNCK'
'ANFR'
'AND'
'ANHM'
'AGGL'
'CRPY'
'CROS'
'CROU'
'CRSC'
'DUM'
'NODO'
'F'
'FALT'
'SSH'
'QSP'
'BIN'
'PYF'
'SMS'
'BLT'
'BFL'
'BFLS'
'BLTS'
'CHF'
'BAT'
'BINI'
'CYL'
'BAU'
'BAUI'
'CYF'
'BFLI'
'PYAR'
'BOY'
'BALS'
'BFL'
'FLZN'
'DSK'
'BAG'
'BMY'
'SMPY'
'STWK'
'DBF'
'FAUL'
'RBER'
'BMYS'
'RFX'
'BAMY'
'BFXS'
'RAT'
'RLAT'
'RFLI'
'RFX'
'RLT'
'RALT'
'RYU'
'GZSX'
'RFL'
'REF'
'ANOM'
'FLSX'
'MSSX'
'BFX'
'RAYL'

UNITS : METRES DATE: 04/03/29 TIME: 14:10:51
DRAWN BY : RGC

Tulsequah Chief Property
Section Azimuth 236

M5

Software by Geosoft Software International

15900.0 N
10800.0 E
15400.0 N
10600.0 E
15200.0 N
10400.0 E
15000.0 N

700.0 m asl
600.0 m asl
500.0 m asl
400.0 m asl
300.0 m asl
200.0 m asl
100.0 m asl
0.0 m asl
-100.0 m asl
-200.0 m asl
-300.0 m asl
-400.0 m asl
-500.0 m asl
-600.0 m asl
-700.0 m asl
-800.0 m asl

LEGEND

LITHOLOGY , ROCKTYPE (LEFT)
MESRED1 , ROCKTYPE (RIGHT)

DI
VI
SMD
QFP
FEDK
EXT
ZNF
CUF
CHT
FEVL
MAGK
ANFR
AND
ANMM
AGGL
ORPY
ORDS
ORSU
ORSC
DUM
NODD
F
FALT
SSH
QSP
BIN
PYF
SMS
BLT
BFL
BFLS
BLTS
CHF
BAT
BINI
CHL
BAU
BAUI
CYF
BFLI
PYAR
BDY
BALS
BFL
FLZN
DSK
BAG
BMY
SMPY
STWK
DBF
FAUL
RSER
BMYS
RFX
BMYY
BFXS
RAT
RLAT
RFLI
RFX
RLT
RALT
RYU
QZSX
RFL
RDF
ANDK
FLSX
MSSX
BFX
RMYL

ASSAYS , ZNPPM (LEFT)

0.0000 - 50.0000
50.0000 - 100.0000
100.0000 - 200.0000
200.0000 - 500.0000
500.0000 - 1000.0000
1000.0000 - 1000000.0000

ASSAYS , CUPPM (RIGHT)

0.0000 - 50.0000
50.0000 - 100.0000
100.0000 - 200.0000
200.0000 - 500.0000
500.0000 - 1000.0000
1000.0000 - 1000000.0000

ASSAYS , ZNPPM (LEFT)

Upper Bound 10000.0000
Lower Bound 1.0000

ASSAYS , CUPPM (RIGHT)

Upper Bound 10000.0000
Lower Bound 1.0000

HOLE-ID
XXX

POLYGON LEGEND

TARGET OUTLINE

HATCH PATTERNS - 'ROCKCODE'

BFLS
RMYL
MSSX
BIN
QSP
STWK

FILL HATCH COLOURS - 'ROCKCODE'

'DI'
'VI'
'SMD'
'QFP'
'FEDK'
'EXT'
'ZNF'
'CUF'
'CHT'
'FEVL'
'MAGK'
'ANFR'
'AND'
'ANMM'
'AGGL'
'ORPY'
'ORDS'
'ORSU'
'ORSC'
'DUM'
'NODD'
'F'
'FALT'
'SSH'
'QSP'
'BIN'
'PYF'
'SMS'
'BLT'
'BFL'
'BFLS'
'BLTS'
'CHF'
'BAT'
'BINI'
'CHL'
'BAU'
'BAUI'
'CYF'
'BFLI'
'PYAR'
'BDY'
'BALS'
'BFL'
'FLZN'
'DSK'
'BAG'
'BMY'
'SMPY'
'STWK'
'DBF'
'FAUL'
'RSER'
'BMYS'
'RFX'
'BMYY'
'BFXS'
'RAT'
'RLAT'
'RFLI'
'RFX'
'RLT'
'RALT'
'RYU'
'QZSX'
'RFL'
'RDF'
'ANDK'
'FLSX'
'MSSX'
'BFX'
'RMYL'

UNITS : METRES DATE: 04/03/29 TIME: 13:45:49
DRAWN BY : RGC

Tulsequah Chief Property
Section Azimuth 225

M6

Software by Geocon Software International

15600.0 N
10000.0 E
15400.0 N
10000.0 E
15200.0 N
10400.0 E
15000.0 N

700.0 m asl
600.0 m asl
500.0 m asl
400.0 m asl
300.0 m asl
200.0 m asl
100.0 m asl
0.0 m asl
-100.0 m asl
-200.0 m asl
-300.0 m asl
-400.0 m asl
-500.0 m asl
-600.0 m asl
-700.0 m asl
-800.0 m asl

LEGEND

LITHOLOGY : ROCKTYPE (LEFT)
NESTED : ROCKTYPE (RIGHT)

DH
VH
SRD
QFP
FEDK
EXT
ZNF
CLF
CHT
FEWL
MAGK
ANFR
AND
AHM
AGGL
QPPY
QRDS
QRSU
QRSC
CLM
NODD
F
FALT
SSH
QSP
BIN
PYF
SMS
BLT
BFL
BFLS
BLTS
CHF
BAT
BINI
CHL
BAU
BAUI
QYF
BFLI
PYWR
BDY
BAUS
BFL
FLDN
QSX
BAG
BMY
SMPY
STMK
DBF
FAUL
RSER
BMYS
RFX
BMWY
BFXS
RAT
RLAT
RFLI
RFX
RLT
RALT
RYU
QZBX
RFL
RDF
AMDK
FLBX
MSSX
BFX
RMYL

ASSAYS : ZNPPM (LEFT)

0.0000 - 50.0000
50.0000 - 100.0000
100.0000 - 200.0000
200.0000 - 500.0000
500.0000 - 1000.0000
1000.0000 - 10000000.0000

ASSAYS : CUPPM (RIGHT)

0.0000 - 50.0000
50.0000 - 100.0000
100.0000 - 200.0000
200.0000 - 500.0000
500.0000 - 1000.0000
1000.0000 - 10000000.0000

ASSAYS : ZNPPM (LEFT)

Upper Bound 10000.0000
Lower Bound 1.0000

ASSAYS : CUPPM (RIGHT)

Upper Bound 10000.0000
Lower Bound 1.0000

XXX
HOLE-ID

POLYGON LEGEND

TARGET OUTLINE

HATCH PATTERNS - 'ROCKCODE'

BFLS
RMYL
MSSX
BIN
QSP
STMK

FILL HATCH COLOURS - 'ROCKCODE'

'DH'
'VH'
'SRD'
'QFP'
'FEDK'
'EXT'
'ZNF'
'CLF'
'CHT'
'FEWL'
'MAGK'
'ANFR'
'AND'
'AHM'
'AGGL'
'QPPY'
'QRDS'
'QRSU'
'QRSC'
'CLM'
'NODD'
'F'
'FALT'
'SSH'
'QSP'
'BIN'
'PYF'
'SMS'
'BLT'
'BFL'
'BFLS'
'BLTS'
'CHF'
'BAT'
'BINI'
'CHL'
'BAU'
'BAUI'
'QYF'
'BFLI'
'PYWR'
'BDY'
'BAUS'
'BFL'
'FLDN'
'QSX'
'BAG'
'BMY'
'SMPY'
'STMK'
'DBF'
'FAUL'
'RSER'
'BMYS'
'RFX'
'BMWY'
'BFXS'
'RAT'
'RLAT'
'RFLI'
'RFX'
'RLT'
'RALT'
'RYU'
'QZBX'
'RFL'
'RDF'
'AMDK'
'FLBX'
'MSSX'
'BFX'
'RMYL'


FILL HATCH COLOURS - 'ROCKCODE'

UNITS : METRES DATE: 04/03/29 TIME: 13:25:46
DRAWN BY : RGC

Tulsequah Chief Property
Section Azimuth 212.5

M7

Software by Geosoft Software International



LEGEND

LITHOLOGY : ROCKTYPE (LEFT)
MESTRO : ROCKTYPE (RIGHT)

- DI
- VA
- SPD
- QFP
- FEDK
- EXT
- ZNF
- CLF
- CHT
- FEVL
- MAGX
- ANFR
- AND
- ANHM
- AGGL
- OPPY
- OPDS
- OPDU
- OPEC
- CLM
- NDCD
- F
- FALT
- SSH
- QSP
- BIN
- PYF
- SHS
- BLT
- BFL
- BFLS
- BLTS
- CHF
- BAT
- BINI
- CHL
- BAU
- BAUI
- CNF
- BFLI
- PYAR
- BDY
- BALS
- BFL
- FLDN
- DSK
- BAG
- EHY
- SMPY
- STWK
- DBF
- FAUL
- RSER
- EHYS
- RFX
- BAHY
- BFXS
- RAT
- RLAT
- RFLI
- RFX
- RLT
- RALT
- RYU
- QZSK
- RFL
- RDF
- AMDK
- FLSK
- MSSX
- BFX
- RHYL

ASSAYS : ZNPPM (LEFT)

- 0.0000 - 50.0000
- 50.0000 - 100.0000
- 100.0000 - 200.0000
- 200.0000 - 500.0000
- 500.0000 - 1000.0000
- 1000.0000 - 1000000.0000

ASSAYS : CUPPM (RIGHT)

- 0.0000 - 50.0000
- 50.0000 - 100.0000
- 100.0000 - 200.0000
- 200.0000 - 500.0000
- 500.0000 - 1000.0000
- 1000.0000 - 1000000.0000

ASSAYS : ZNPPM (LEFT)

Upper Bound 10000.0000
Lower Bound 1.0000

ASSAYS : CUPPM (RIGHT)

Upper Bound 10000.0000
Lower Bound 1.0000

HOLE-ID
XXX

POLYGON LEGEND

TARGET OUTLINE

HATCH PATTERNS - 'ROCKCODE'

- BFLS
- RHYL
- MSSX
- BIN
- QSP
- STWK

FILL HATCH COLOURS - 'ROCKCODE'

'DI'
'VA'
'SPD'
'QFP'
'FEDK'
'EXT'
'ZNF'
'CLF'
'CHT'
'FEVL'
'MAGX'
'ANFR'
'AND'
'ANHM'
'AGGL'
'OPPY'
'OPDS'
'OPDU'
'OPEC'
'CLM'
'NDCD'
'F'
'FALT'
'SSH'
'QSP'
'BIN'
'PYF'
'SHS'
'BLT'
'BFL'
'BFLS'
'BLTS'
'CHF'
'BAT'
'BINI'
'CHL'
'BAU'
'BAUI'
'CNF'
'BFLI'
'PYAR'
'BDY'
'BALS'
'BFL'
'FLDN'
'DSK'
'BAG'
'EHY'

UNITS : METRES DATE: 04/03/29 TIME: 12:59:12
DRAWN BY : RGC


Tulsequah Chief Property
Section Azimuth 200

MB

Software by Geosoft Software International

15600.0 N | 10800.0 E | 15400.0 N | 10600.0 E | 15200.0 N | 10400.0 E | 15000.0 N

700.0 m asl
600.0 m asl
500.0 m asl
400.0 m asl
300.0 m asl
200.0 m asl
100.0 m asl
0.0 m asl
-100.0 m asl
-200.0 m asl
-300.0 m asl
-400.0 m asl
-500.0 m asl
-600.0 m asl
-700.0 m asl
-800.0 m asl



LEGEND

LITHOLOGY : ROCKTYPE (LEFT)
NESTED : ROCKTYPE (RIGHT)



- DI
- VA
- SPD
- QFP
- FEDK
- EXT
- ZNF
- CLF
- CHT
- FEML
- MAGK
- AMFR
- AND
- AMM
- AGGL
- QPPY
- QMDS
- QMSU
- QMSC
- CLM
- NCCO
- F
- FALT
- SSM
- QSP
- BIN
- PYF
- SMS
- BLT
- BFL
- BFLS
- BLTS
- CHF
- BAT
- BINI
- CHL
- BAU
- BAUI
- DYF
- BFLI
- PYAR
- BDY
- BAUS
- BFL
- FLZN
- CSX
- BAG
- BHY
- SMPY
- STWK
- DBF
- FAUL
- RBER
- BMYS
- RFX
- BMYF
- BFYS
- RAT
- RLAT
- RFLI
- RFX
- RLT
- RALT
- RYU
- QZBX
- RFL
- RDF
- AMDK
- FLSX
- MSSX
- BFX
- RHYL

ASSAYS : ZNPPM (LEFT)

0.0000 –	50.0000
50.0000 –	100.0000
100.0000 –	200.0000
200.0000 –	500.0000
500.0000 –	1000.0000
1000.0000 –	1000000.0000

ASSAYS : CUPPM (RIGHT)

0.0000 –	50.0000
50.0000 –	100.0000
100.0000 –	200.0000
200.0000 –	500.0000
500.0000 –	1000.0000
1000.0000 –	1000000.0000

ASSAYS : ZNPPM (LEFT)
Upper Bound 10000.0000
Lower Bound 1.0000

ASSAYS : CUPPM (RIGHT)
Upper Bound 10000.0000
Lower Bound 1.0000

POLYGON LEGEND

TARGET OUTLINE

HATCH PATTERNS - 'ROCKCODE'



FILL HATCH COLOURS - 'ROCKCODE'

UNITS : METRES DATE: 04/03/30 TIME: 09:54:20
DRAWN BY : RGC

Tulsequah Chief Property
Section Azimuth 190

M9

Software by Geosoft Software International