

Report on
Geochemical Surveys and Trenching
on the

Aumax Property
Aumax #1 to #6 Claims

Lillooet Mining Division
British Columbia
Canada

N.T.S.: 092 J/09

UTM co-ord.: 567,700 m E, 5,601,400 m N
NAD 83, Zone 10

Owner/Operator:

Avino Silver & Gold Mines Ltd.
Suite 400 – 455 Granville Street
Vancouver, B.C. V6C 1H1

Author:

David St. Clair Dunn, P. Geo.
1154 Marine Drive
Gibsons, B.C. V0N 1V1

November 15, 2004

GEOLOGICAL SURVEY BRANCH
MINERAL ASSESSMENT BRANCH

Table of Contents

	Page
Introduction	1
2004 Geochemical Surveying and Trenching Program	2
Interpretation and Conclusions	3
References	4

List of Figures

	Following Page
Figure 1: General Location Map	1
Figure 2: Claim Location Map	2
Figure 3: Compilation Map – Aumax Zone	3
Figure 4: Upper Zone – Soil Geochemical Survey – Trench	4

List of Tables

	Page
Table 1: Table of Mineral Claims	1

List of Appendices

Appendix A: Cost Statement

Appendix B: Sample Descriptions

Appendix C: Assay Results and Assay Procedure

Appendix D: Author's Statements of Qualifications

Introduction

The Aumax Property (the property) is located on the east side of Cayoosh Creek, 16 kilometers southwest of the town of Lillooet (Fig. 1 & 2). The property can be accessed from Lillooet by taking Highway 99 twenty-three kilometres southwest to a logging road which branches east off the Highway. Follow this logging road approximately eight kilometers easterly to the area of the Aumax Showing (Fig. 3). The Upper Zone can be accessed by hiking a further 1.5 km. southwest or by a 20 minute helicopter flight from Lillooet.

The 2004 geochemical survey and trenching program was carried out mainly on the Upper Zone, with 136 soil samples and seven rock samples collected in this area during a four day, helicopter supported program (Fig. 4). Thirty-one soil samples and seven rock samples were collected in the area of the Aumax showing during a two day truck supported program (Fig. 3).

The property consists of six located mineral claim covering 39 units as listed below:

Table 1: Table of Mineral Claims

Claim Name	Tenure Number	Number Units	Expiry Date (Assuming Report Accepted)
Aumax # 1	368966	20	01/09/06
Aumax # 2	368967	15	01/09/06
Aumax # 3	371390	1	01/09/06
Aumax # 4	371391	1	01/09/06
Aumax # 5	371392	1	01/09/06
Aumax # 6	371393	1	01/09/06

The mineral claims are owned by Avino Silver and Gold Mines Ltd. Avino was the operator of the 2004 program and contracted the author to provide geological supervision.

The property is located between Cayoosh Creek and Phair Creek. The showings are new discoveries, made in 1999 by Randy and Gary Polischuk. The discovery of the Aumax showing was made during logging road construction and of the Upper Zone during follow-up prospecting. Both showings have economically interesting gold and silver values. Mr. Randy Polischuk staked the showings and subsequently sold them to the company.

Cayoosh Creek has a history of limited placer gold production starting in the 1860's. Some of this production occurred immediately downstream of the property, near the mouth of Downtown Creek (Fig. 2).



Aumax Property

Aumax Property

Avino Silver & Gold Mines Ltd.

Aumax Property
Lillooet Mining District, B.C., Canada

Location Map

Scale	as shown	N.T.S.	92J/09	Figure	1
Date	November 2004	U.T.M. Zone	10		
By	A.G.B.	David Dunn, P.Geo			

A limited exploration program of prospecting, rock and soil sampling and mechanized trenching was carried out in October, 1999 (Pickett, 2002). Trenching on the Aumax showing was inconclusive. Many highly anomalous quartz-carbonate boulders, up to 2.2 g/t gold and 305 g/t silver, were excavated but bedrock was not reached in critical areas (Fig. 3). Chip samples of veins exposed in the trenches were highly anomalous, generally in the hundreds of ppbs gold, with one sample over one g/t gold over 0.5 metres. Pickett concluded that the source of the anomalous boulders was uphill to the southeast. Pickett recommended further prospecting and soil sampling southeast (upslope) of the Aumax showing.

Limited soil sampling and prospecting in 1999 on the Upper Zone returned extremely anomalous soil samples to 4560 ppb gold. Pickett recommended grid geochemical sampling and further prospecting in this area.


2004 Geochemical Surveying and Trenching Program

The 2004 geochemical surveying and trenching program was designed to carry out the recommendations of Pickett, 2002. All work was carried out on the Aumax # 1 mineral claim.

The author, accompanied by R. Polischuk the first day, carried out initial reconnaissance mapping of the Aumax showing and soil sampling above the showing on the 16th and 17th of June, 2004. Previous to this work, the access road to the Aumax showing was reopened with an excavator. This involved 19.5 hours work with a 325 Caterpillar excavator to clear boulders and two small slides blocking the road.

Thirty-one soil samples were taken at 10 metre intervals from 30 to 60 cm. depth in a well developed "B" horizon on the 1675 metre asl contour line starting at 566,487 m E, 5,602,023 m N and proceeding northeast (Fig. 3). This line was run approximately 200 metres upslope to the southeast of the main Aumax showing.

Structural mapping was carried out in the area of the Aumax showings which shows the main showing is at the junction of four faults and that the 1999 trenching did not test the main north-south structure or a mineralized east-west structure (Fig. 3).



(from Mineral Titles Reference Map 92J/09E, B.C. Ministry of Energy and Mines)

Avino Silver & Gold Mines Ltd.			
Aumax Property			
Lillooet Mining District, B.C., Canada			
Claim Map			
Scale	as shown	N.T.S.	92J/09
Date	June 2004	U.T.M.	zone 10
By	A. Barrett	David Dunn, P.Geo	


A two person crew was mobilized by helicopter to the Upper Zone on the property August 9, 2004 and demobilized August 13, 2004. A grid controlled soil geochemical sampling survey was carried out over the Upper Zone. A base line was run due north 300 metres from 567,300 m E 5,601,370 m N. Samples were taken at 10 metre intervals on the base line and seven east-west lines run from 567,150 m E to 567,350 m E (except 1620: 250-350 m E) at 50 metre intervals from 5,601,370 m N to 5,601,620 m N. Samples were taken at 20 to 40 cm. depth from a poorly developed "B" soil horizon with fragments greater than two cm. sorted out. Grid, soil and rock sample locations and some geological information are shown on Fig. 4. A trench was excavated to bedrock by hand immediately upslope of the site of the soil sample containing 4560 ppb gold from the 1998 sample. Six chip samples were taken across the exposed fault zone (Appendix B). Geological and structural mapping were carried out in the grid area.

Interpretation and Conclusions

The soil geochemical line run upslope from the Aumax showing returned some weakly anomalous values in gold, up to 72 ppb Au, and arsenic, up to 984 ppm (Appendix C). These values, and the lack of anomalous values for other elements, especially silver, imply that there are no highly mineralized zones under or immediately upslope from the soil line. Geological mapping shows that the area where most of the mineralized boulders were excavated in 1999 is at the junction of four fault zones. The soil line and the geological information indicate that the mineralization did not come from upslope but from the area of the fault junctions where the mineralized boulders were excavated. Tr-99-02 did not reach outcrop in its north end where the main north-south fault is projected to be. This area is probably the source of the mineralized boulders and should be trenched to bedrock so the fault can be mapped and sampled (Fig. 3).

Two hundred metres northeast mapping shows that TR-99-03 did not test a major east-west mineralized structure. This structure should be trenched to bedrock, sampled and mapped.

The soil grid sampled on the Upper showing returned highly anomalous values in gold to 3.82 g/t, silver to 16.2 g/t and arsenic greater than 1%. These anomalous sample outlined a discreet area, 100 metres by 200 metres, of highly anomalous gold, silver and arsenic values (Fig. 4). This area trends northwesterly and overlies a number of fault zones trending 150° and dipping vertically. These fault zones are variably silicified and sericitized and are in andesitic volcanic host rocks in the area of the soil grid. Pyrite and minor arsenopyrite are seen in the faults. The anomaly is obscured by the remnants of a lateral moraine to the northwest but the structures can be seen continuing at least 500 metres to the southeast.



LEGEND

- Access road
- Creek
- Contour (20m interval)
- Geological fault
Dip & strike
- Trench (1999)
- Trench (proposed)
- 198861 Sample (Dunn, 2004)

100 metres

Avino Silver & Gold Mines Ltd.

Aumax Property
Lillooet Mining District, B.C., Canada

AUMAX ZONE
Compilation Map


Scale	as shown	N.T.S.	921/09	Figure 3
Date	June 2004	U.T.M.	zone 10	
By	A. Barrett/ D. Dunn		David Dunn, P.Geo	

(from B. Malahoff, 1999, via W. Pickett, 2002)

Chip samples in Trench # 1 did not return any values of economic interest, and no values high enough to explain the very high gold values in soil samples a few metres away. It must be concluded that the mineralization manifested by the very high gold values in soil has not been exposed. Further trenching is strongly recommended, either with a focused program of helicopter supported hand trenching or using a helicopter portable excavator, to expose and sample the mineralized fault zones (Fig. 4). In conjunction with this work, the southeastern extension of the mineralized structure should be prospected, sampled and mapped in detail.


The recommended work programs should take two weeks to complete and are estimated to cost \$22,000.

Respectfully submitted,

A handwritten signature in black ink is written over a circular professional seal. The seal contains the text: "PROFESSIONAL", "PROVINCE OF", "D. S. C. DUNN", "BRITISH COLUMBIA", and "GEOSCIENTIST".

References

Pickett, J. W., 2002, Technical Report on the Aumax Property, for Avino Silver & Gold Mines Ltd.



LEGEND

- Creek
- Contour (20m interval)
- Geological contact
- Geological fault
- Trench (2004)
- Trench (proposed)
- Rock sample
- Soil geochemical grid (Au [ppb])
- Gold in soil, >100 ppb contour
- Silver in soil, >1.0 ppm
- Arsenic in soil, >1,000 ppm

Avino Silver & Gold Mines Ltd.
Aumax Property
 Lillooet Mining District, B.C., Canada

UPPER ZONE
Soil Geochemistry & Trench

Scale	1:1,000	N.T.S.	92J/09	Figure	4
Date	June 2004	U.T.M.	zone 10		
By	A. Barrett/ D. Dunn		David Dunn, P.Geo		

Appendix A
Cost Statement

Appendix A: Cost Statement

Aumax Showing


Excavator (CAT 325): 19.5 hours @ \$120/hr	\$2,340
Mob/demob	400
Geologist (D. Dunn) 15-17/6/04 @ \$500/day	1,500
Expenses (R+B, Truck rental, fuel etc.)	754
Technician (R. Polischuk) 16/6/04 @ \$325/day	325
Assays (31 soils, 9 rocks)	843

Upper Zone

Helicopter (Caribou-Chilcotin) 1.4 hours @ ~ \$1,080/hr	1,511
Geologist (D. Dunn) 9-13/8/04 @ \$500/day	2,500
Technician (A. Barrett) 9-13/8/04 @ \$250/day	1,250
Expenses (Food, transportation, expendables)	433
Assays (136 soils, 7 rocks)	3,114

Report Preparation 2,500

Total Costs



Appendix B

Sample Descriptions

Appendix B: Sample Descriptions

Aumax Showing

- Sample 198855 (566,551 m E, 5,607,551 m N)– Flt. 0.5 m diameter (dia) felsic dyke w/ 5% su. Silvery grey metallic. Tetrahedrite? Multiple < cobbles in road cut. Top layer of slope w/sulphides is rubble, not glacial till.
- Sample 198856 same location 198855 – Flt. 0.3 m dia silicified sediment w/ 1% py + fine silvery metallic.
- Sample 198857 Grab in roadcut. Andesite w/ 1% py + qtz str S 0° D 28° E every 10-30 cm.
- Sample 198858 (565,768 m E, 5,602,923 m N) Grab. Very rusty foliated o/c.
- Sample 198859 (566,036 m E, 5,602,395 m N) Grab. And. w/ qtz str S 120° D 70° S.
- Sample 198860 (566,233 m E, 5,602,395 m N) Grab. Strongly carb. Alt. + sil. Phyllite. S 88° D 70° S.
- Sample 198861 (566,178 m E, 5,602,182 m N) 1.2 m chip across sil. Shear zone w/ 1% py S 65° D 80° N in phyllite on strike TR-99-01 + 02.
- Sample 198862 (566,377 m E, 5,662,403 m N) 1.2 m chip of shear zone in phyllite w/ str carb alt. S 52° D 80° N. Minor py.
- Sample 198863 (566,480 m E, 5,662,401 m N) 1.5 m chip of qtz vn. Footwall of 5 m wide shear zone S 32° D 65° N in phyllite.

Upper Zone

- Sample 68801 (567,297 m E, 5,601,395 m N) 1.5 m chip of qtz vn. Minor FeOx. S 165° D 80° W.
- Sample 68802 (567,232 m E, 5,601,531 m N) 1.0 m chip Tr # 1 E-W from E end. Silicified, schistose andesite tuff. V. minor grey metallic. Aspy? Schistosity + s of Fr. S 165° D 70° W.
- Sample 68803 Tr # 1 W of 02. 1.0 m chip And. alt. to serp.
- Sample 68804 Tr # 1 W of 03. 1.0 m chip. Serp. And. ++ Ca CO₃.
- Sample 68805 Tr # 1 W of 04. 1.0 m chip. Chlorite, sericite, minor antigorite, py.
- Sample 68806 Tr # 1 W of 05. 1.0 m chip. Chlorite, sericite schist, minor py.
- Sample 68807 Tr # 1 W of 06. 1.0 m chip And. w/ carb. Minor talc, v. minor py.

Appendix C

Assay Results and Assay Procedure



GEOCHEMICAL ANALYSIS CERTIFICATE



Ayino Silver & Gold Mines Ltd. PROJECT AUMAX File # A402908
400 - 455 Granville St., Vancouver BC V6G 1T1

07/08/04

14:36

604 6823600

ONIVA INT. A SERV

008

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	Le	Cr	Hg	Ba	Ti	B	Al	Na	K	W	Au**	Pt**	Pd**	Sample
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	%	ppm	ppm	%	ppm	%	%	%	%	%	ppm	ppb	ppb	ppb	kg
S1	<1	<1	<3	<1	<.3	<1	<1	2	<.01	<2	<8	<2	<2	2	<.5	<3	<3	<1	.11	<.001	<1	<1	<.01	3	<.01	<3	.01	.49	.01	<2	<2	<2	<2	-
198855	3	269	8	30	.5	45	41	476	5.34	12	<8	<2	<2	21	<.5	<3	4	59	1.16	.133	1	33	.51	20	.34	<3	.77	.10	.09	<2	6	<2	<2	2.76
198856	1	21	<3	16	<.3	13	6	1167	1.35	21	<8	<2	<2	114	<.5	<3	<3	4	4.11	.036	4	<1	.49	32	<.01	<3	.20	.01	.10	<2	6	<2	<2	.95
198857	1	76	<3	90	<.3	110	38	759	5.07	7	<8	<2	<2	25	<.5	<3	<3	144	1.69	.101	1	248	2.08	31	.32	<3	2.53	.11	.24	2	12	<2	<2	1.13
198858	2	45	4	16	<.3	4	1	106	1.41	<2	<8	<2	5	9	<.5	<3	<3	20	.08	.019	12	5	.44	152	.02	<3	.78	.02	.41	2	5	<2	4	1.48
198859	2	267	3	63	.6	82	40	572	5.77	<2	<8	<2	<2	26	.5	<3	<3	94	1.32	.162	3	78	1.16	17	.39	<3	1.47	.06	.10	2	11	<2	<2	1.01
198860	1	88	<3	45	1.1	29	18	1536	3.40	1151	<8	<2	<2	62	<.5	4	<3	45	2.29	.054	7	11	.70	49	.01	<3	.74	.02	.18	2	69	<2	<2	1.47
198861	2	49	5	30	<.3	19	5	1276	1.47	26	<8	<2	<2	4	<.5	<3	<3	6	.05	.014	3	<1	.03	58	<.01	<3	.18	<.01	.07	4	3	<2	15	1.32
198862	2	74	<3	92	.9	120	34	1660	6.96	1516	<8	<2	<2	83	<.5	<3	<3	27	5.07	.077	4	56	.41	81	<.01	<3	.77	.03	.26	<2	52	<2	4	1.68
198863	2	54	<3	55	7.7	25	13	814	3.33	3271	<8	<2	<2	27	<.5	8	<3	9	2.00	.053	8	6	.05	41	<.01	<3	.25	<.01	.17	4	203	<2	3	2.49
STANDARD	13	145	26	133	<.3	26	12	755	3.01	18	10	<2	3	47	5.7	4	5	61	.74	.092	12	183	.69	139	.10	16	2.00	.04	.15	5	487	491	489	-

Standard is STANDARD DS5/FA-10R.

GROUP 1D - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY ICP-ES.

(>) CONCENTRATION EXCEEDS UPPER LIMITS. SOME MINERALS MAY BE PARTIALLY ATTACKED. REFRACTORY AND GRAPHITIC SAMPLES CAN LIMIT AU SOLUBILITY.


ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB

- SAMPLE TYPE: ROCK R150 60C AU** PT** & PD** GROUP 3B BY FIRE ASSAY & ANALYSIS BY ICP-ES. (30 gm)

Data h FA _____

DATE RECEIVED: JUN 21 2004

DATE REPORT MAILED: July 2/04...





GEOCHEMICAL ANALYSIS CERTIFICATE



Avalo Silver & Gold Mines Ltd. PROJECT RUDAX File # A402907

100 - 85 Granville St. Vancouver, BC V6C 1T1

07/08/04

14:35

804 6823600

ONTA INT. A SERV

005

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Tl	B	Al	Na	K	W	Au**	Pt**	Pd**
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	%	ppm	ppm	%	ppm	%	%	%	%	%	ppm	ppb	ppb	ppb
G-1	2	1	<3	37	<3	4	4	508	1.88	<2	<8	<2	5	83	<5	<3	<3	41	.61	.087	9	49	.52	200	.14	<3	.87	.09	.46	<2	<2	<2	<2
L1 3+00N	5	80	5	171	.5	70	28	678	5.87	147	<8	<2	2	12	<5	<3	<3	90	.17	.227	18	58	1.05	168	.01	<3	2.47	.01	.14	3	7	<2	<2
L1 2+90N	2	36	8	105	.6	31	20	618	3.70	125	<8	<2	<2	11	<5	<3	<3	79	.29	.083	10	37	.72	83	.10	<3	1.77	.01	.08	2	49	<2	<2
L1 2+80N	3	28	7	90	.7	29	10	227	2.96	59	<8	<2	2	7	<5	4	<3	48	.17	.058	17	23	.32	95	.04	<3	1.29	.01	.09	2	20	2	<2
L1 2+70N	3	40	4	135	.5	48	23	815	4.19	102	<8	<2	2	10	<5	<3	<3	87	.23	.169	8	61	.97	95	.11	3	2.39	.01	.09	2	5	<2	<2
L1 2+60N	1	19	8	94	.3	22	12	608	2.81	21	<8	<2	<2	8	<5	<3	<3	63	.16	.147	5	26	.57	83	.11	<3	1.42	.01	.06	<2	66	<2	<2
L1 2+50N	2	41	10	166	.5	48	20	705	3.90	50	<8	<2	<2	10	<5	3	<3	70	.20	.095	11	44	.63	185	.06	<3	1.96	.01	.09	3	10	<2	<2
L1 2+40N	1	27	12	139	<3	35	18	866	3.41	24	<8	<2	2	11	<5	<3	<3	62	.27	.173	10	41	.62	175	.08	3	1.73	.01	.13	2	21	<2	<2
L1 2+30N	2	22	10	110	.3	27	13	738	3.02	62	<8	<2	<2	8	<5	<3	<3	62	.16	.117	9	31	.39	117	.06	<3	1.39	.01	.09	2	14	<2	<2
L1 2+20N	2	57	10	161	.4	61	25	1023	4.94	232	<8	<2	2	12	<5	4	<3	92	.29	.119	11	63	.78	177	.02	4	2.18	.01	.13	2	18	<2	<2
L1 2+10N	1	32	17	153	1.0	42	18	599	4.20	984	<8	<2	2	17	<5	3	<3	69	.37	.076	9	46	.55	163	.03	<3	2.33	.01	.08	2	14	<2	<2
L1 2+00N	3	69	8	136	.6	87	33	748	5.68	202	<8	<2	2	14	<5	3	<3	126	.36	.061	11	124	1.49	136	.10	3	2.86	.01	.09	2	7	<2	<2
L1 1+90N	3	64	9	127	.3	75	35	877	5.34	149	<8	<2	3	17	<5	<3	<3	117	.28	.042	13	68	1.35	138	.07	5	2.91	.01	.07	<2	12	<2	<2
L1 1+80N	2	50	<3	107	<3	62	30	899	5.24	109	<8	<2	2	17	<5	<3	<3	123	.45	.083	7	82	1.20	145	.10	4	2.52	.01	.11	2	45	<2	<2
L1 1+70N	1	85	8	116	3.4	67	30	540	5.79	847	<8	<2	2	9	<5	4	<3	85	.15	.056	10	48	.69	119	.02	<3	2.03	.01	.09	2	72	<2	<2
L1 1+60N	2	56	5	121	<3	78	32	1210	4.98	165	<8	<2	<2	16	<5	<3	<3	97	.48	.088	6	104	1.23	123	.17	<3	2.52	.01	.11	2	11	<2	<2
L1 1+50N	2	51	9	119	.8	64	25	582	4.88	175	<8	<2	2	14	.5	<3	<3	95	.29	.085	9	69	.90	127	.13	<3	2.67	.01	.11	<2	6	<2	<2
L1 1+40N	2	37	4	136	<3	51	18	658	4.44	118	<8	<2	2	11	<5	<3	<3	91	.23	.122	11	68	.80	136	.11	<3	2.14	.01	.11	<2	11	2	<2
RE L1 1+40N	2	36	6	140	<3	52	19	667	4.47	115	<8	<2	2	11	<5	<3	<3	92	.23	.123	11	68	.80	136	.10	<3	2.16	.01	.11	2	-	-	-
L1 1+30N	1	35	9	92	.3	45	16	760	3.71	81	<8	<2	2	12	<5	<3	<3	76	.23	.082	13	54	.73	128	.09	<3	1.87	.01	.11	2	12	<2	<2
L1 1+20N	3	39	8	143	.3	53	20	688	4.67	127	<8	<2	2	11	<5	3	<3	95	.23	.130	11	69	.84	140	.10	<3	2.25	.01	.11	2	8	2	<2
L1 1+10N	2	80	6	159	.3	83	28	699	5.54	170	<8	<2	2	9	<5	5	<3	91	.23	.105	13	88	1.14	133	.11	<3	2.35	.01	.12	2	15	2	<2
L1 1+00N	<1	19	7	76	<3	22	9	298	2.66	55	<8	<2	<2	7	<5	<3	<3	62	.13	.064	8	30	.38	75	.08	<3	1.37	.01	.06	2	3	<2	<2
L1 0+90N	5	78	8	146	.6	63	22	706	5.12	193	<8	<2	2	9	<5	3	<3	75	.16	.113	14	50	.80	144	.05	<3	1.92	.01	.09	3	10	<2	<2
L1 0+80N	3	48	8	149	<3	52	18	962	4.22	109	<8	<2	2	12	<5	<3	<3	63	.29	.110	15	39	.49	162	.04	<3	1.62	.01	.17	2	13	<2	<2
L1 0+70N	3	99	6	155	.3	67	22	571	5.26	267	<8	<2	4	7	<5	5	<3	59	.10	.078	20	31	.54	73	.04	<3	1.34	<.01	.11	3	28	2	<2
L1 0+60N	5	59	11	167	<3	53	24	1237	4.81	53	8	<2	2	15	<5	<3	<3	81	.18	.108	16	43	.78	162	.02	<3	2.25	.01	.16	3	6	2	<2
L1 0+50N	4	47	12	159	<3	43	14	578	5.46	56	<8	<2	2	13	<5	<3	<3	73	.20	.163	12	42	.55	141	.04	<3	2.18	.01	.10	2	46	2	5
L1 0+40N	3	39	7	124	.3	41	15	495	4.09	104	<8	<2	2	11	<5	3	<3	75	.18	.077	13	44	.61	150	.06	<3	1.96	.01	.10	3	4	<2	<2
L1 0+30N	4	48	8	132	<3	50	18	427	4.50	153	<8	<2	2	13	<5	4	<3	60	.23	.095	13	28	.38	130	.01	<3	1.66	.01	.11	3	56	<2	<2
L1 0+20N	4	96	14	166	<3	64	25	857	6.14	131	<8	<2	3	16	<5	<3	<3	81	.27	.109	20	42	.76	187	.02	<3	2.31	.01	.14	3	35	<2	<2
L1 0+10N	3	45	7	153	.3	59	25	754	4.83	154	<8	<2	2	15	<5	<3	<3	74	.28	.146	13	55	.81	151	.06	<3	2.17	.01	.14	3	11	<2	<2
L1 0+00N	2	50	6	168	<3	60	23	740	4.33	204	<8	<2	2	13	<5	3	<3	67	.27	.133	12	47	.73	141	.06	<3	2.10	.01	.12	4	14	<2	<2
STANDARD DS5/FA-100S	13	147	24	137	.3	26	12	772	3.03	19	10	<2	3	46	5.3	5	7	62	.76	.094	11	189	.70	144	.11	16	1.99	.04	.15	6	47	50	51

GROUP 10 - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 NCL-NH03-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY ICP-ES.
(>) CONCENTRATION EXCEEDS UPPER LIMITS. SOME MINERALS MAY BE PARTIALLY ATTACKED. REFRACTORY AND GRAPHITIC SAMPLES CAN LIMIT AU SOLUBILITY.
- SAMPLE TYPE: SOIL SS80 60C AU** PT** & PD** GROUP 3B BY FIRE ASSAY & ANALYSTS BY ICP-ES. (30 gm)
Samples beginning 'RE' are Retruns and 'RRE' are Reject Retruns.

Data W FA _____ DATE RECEIVED: JUN 21 2004 DATE REPORT MAILED: July 2/04



All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.



GEOCHEMICAL ANALYSIS CERTIFICATE



Avino Silver & Gold Mines Ltd. File # A404613
400 - 455 Granville St., Vancouver BC V6C 1T1

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Au**
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	%	ppm	ppm	%	ppm	%	%	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	gm/mt
SI	.1	.6	.9	1	.1	.3	<.1	<.1	.04	<.5	<.1	<.5	<.1	2	<.1	<.1	<.1	<.1	.11	<.001	<.1	1.8	<.01	3	<.001	<.1	.01	.482	<.01	.1	.01	<.1	<.1	<.05	<.1	<.5	.02
68801	1.1	3.5	1.2	3	.2	3.3	.6	30	.44	322.9	<.1	24.4	.1	2	<.1	.7	<.1	<.1	.01	.002	1	8.9	<.01	10	<.001	1	.04	.009	.01	1.6	.01	.9	<.1	.07	<.1	<.5	.04
68802	.3	91.0	1.1	99	.1	32.1	34.2	1425	7.56	4.6	.1	2.2	.2	25	.2	.3	.3	206	1.21	.069	2	57.9	3.13	51	.472	20	3.86	.021	.10	.4	<.01	15.4	.1	<.05	11	<.5	.01
68803	.5	90.3	1.9	91	.1	30.6	33.0	1237	6.60	4.1	.1	27.4	.2	27	.2	.4	2.3	188	1.52	.073	2	41.4	2.96	33	.444	26	3.42	.018	.07	.4	.01	13.5	.1	<.05	11	.6	.06
68804	.2	94.4	.5	53	.1	26.5	23.2	660	4.31	5.8	.1	1.6	.3	21	.1	.2	<.1	116	1.07	.067	3	34.2	2.04	26	.389	26	2.30	.025	.03	.4	.01	7.1	<.1	<.05	7	<.5	<.01
68805	.4	108.4	.6	72	.1	31.1	32.9	1044	6.27	8.3	.2	1.2	.3	23	.1	.3	<.1	170	1.25	.073	3	35.1	2.87	34	.429	68	3.31	.019	.02	.4	<.01	12.1	<.1	<.05	10	.6	.01
68806	.4	124.8	.4	88	.1	35.1	42.0	1150	7.77	6.1	.3	.7	.3	29	.1	.3	<.1	196	1.17	.087	3	31.6	3.26	30	.389	50	3.94	.015	.03	.4	<.01	15.6	<.1	<.05	12	<.5	<.01
68807	.5	103.5	.9	92	.3	37.1	42.1	1327	8.12	92.1	.2	2.2	.3	37	.1	.5	<.1	183	1.50	.100	4	30.9	2.51	60	.281	26	3.45	.015	.11	.4	.02	15.0	.1	<.05	13	<.5	.01
STANDARD DS5/AU-1	12.3	143.0	24.6	135	.3	24.6	11.8	737	2.95	19.0	6.2	39.8	2.6	50	5.6	3.4	5.8	63	.73	.086	13	189.0	.69	137	.101	16	2.01	.035	.15	4.4	.16	3.6	1.1	<.05	7	5.1	3.39

GROUP 1DX - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY ICP-MS.
(>) CONCENTRATION EXCEEDS UPPER LIMITS. SOME MINERALS MAY BE PARTIALLY ATTACKED. REFRACTORY AND GRAPHITIC SAMPLES CAN LIMIT AU SOLUBILITY.
- SAMPLE TYPE: ROCK R150 60C AU** BY FIRE ASSAY FROM 1 A.T. SAMPLE.

Data & FA _____ DATE RECEIVED: AUG 16 2004 DATE REPORT MAILED: Sept 2/04





GEOCHEMICAL ANALYSIS CERTIFICATE



Avino Silver & Gold Mines Ltd. File # A404614
400 - 455 Granville St., Vancouver BC V6C 1T1

Page 1

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Au**	Pt**	Pd**
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	%	ppm	ppm	%	ppm	%	%	%	%	%	ppm	ppb	ppb	ppb
G-1	2	1	<3	43	<.3	4	4	510	1.77	<2	<8	<2	3	75	<.5	<3	<3	36	.48	.079	6	42	.55	259	.13	<3	.99	.10	.55	<2	5	<2	<2
BL 16+20N	5	121	8	177	<.3	96	29	1139	6.65	453	<8	<2	3	14	.9	<3	<3	86	.18	.073	18	81	1.52	102	.04	<3	2.94	.01	.18	<2	49	<2	<2
BL 16+10N	4	84	8	146	.4	71	25	1297	5.44	203	<8	<2	<2	21	.6	3	<3	75	.30	.101	12	71	1.29	262	.04	<3	2.65	.01	.11	<2	17	<2	<2
BL 16+00N	4	56	14	174	.4	44	29	3508	3.86	220	<8	<2	<2	34	2.1	4	<3	47	.58	.192	10	32	.47	228	.02	<3	1.21	.01	.17	<2	28	2	2
BL 15+90N	3	39	6	114	.7	35	14	1652	3.38	94	<8	<2	<2	12	1.0	<3	<3	53	.15	.123	9	40	.56	181	.02	<3	2.60	.01	.06	2	26	<2	<2
BL 15+80N	7	101	17	192	.5	74	29	1803	5.97	932	<8	<2	2	22	<.5	5	<3	69	.26	.115	15	50	.65	246	.01	<3	2.16	.01	.08	2	371	<2	<2
BL 15+70N	10	156	40	211	.8	97	34	2748	6.50	1011	<8	<2	4	34	.6	7	<3	69	.41	.111	21	48	.76	431	.01	<3	2.20	.01	.14	<2	478	<2	<2
BL 15+60N	9	178	23	272	1.1	144	55	3345	7.58	1267	<8	<2	4	17	1.2	15	3	59	.24	.109	27	67	.86	188	.01	4	2.11	<.01	.15	<2	325	<2	<2
BL 15+50N	5	76	9	145	.6	47	20	2129	4.39	341	<8	<2	2	13	.7	3	<3	58	.13	.213	17	47	.73	124	.05	<3	2.23	.01	.14	<2	73	<2	<2
BL 15+40N	3	72	7	138	1.2	64	22	740	5.18	1046	<8	<2	<2	17	.5	4	<3	73	.28	.106	19	55	1.15	107	.03	<3	2.35	.01	.10	2	147	<2	<2
BL 15+30N	5	91	6	129	<.3	62	17	827	4.64	270	<8	<2	2	13	.5	<3	<3	51	.17	.075	14	47	.71	99	.03	<3	1.79	.01	.09	<2	52	<2	<2
BL 15+20N	4	93	8	135	1.7	74	23	1147	5.19	794	<8	<2	2	15	.5	6	<3	54	.23	.105	17	49	.76	118	.02	<3	1.88	.01	.11	3	171	<2	<2
BL 15+10N	7	125	13	259	2.4	158	34	3039	5.21	1993	<8	<2	3	20	2.5	23	<3	23	.39	.138	33	16	.19	111	<.01	<3	.76	<.01	.06	<2	187	2	2
BL 15+00N	3	133	9	271	7.2	141	46	1492	11.53	>10000	<8	<2	2	63	<.5	37	<3	29	.66	.380	41	29	.29	191	.01	5	1.64	<.01	.08	3	3620	2	<2
BL 14+90N	5	119	22	250	15.6	126	51	2189	10.10	>10000	<8	<2	2	98	.8	34	<3	32	.37	.269	20	29	.38	117	.01	3	1.31	.03	.10	3	3084	<2	<2
RE BL 14+90N	3	117	21	248	15.7	122	50	2163	9.94	>10000	<8	<2	2	96	.8	34	<3	30	.36	.266	20	25	.36	114	.01	<3	1.28	.03	.10	<2	-	-	-
BL 14+80N	5	122	11	181	3.4	95	31	1319	6.83	2901	<8	<2	3	19	.8	11	<3	53	.21	.117	24	53	.80	110	.01	<3	1.87	.01	.10	<2	285	<2	2
BL 14+70N	8	115	22	170	.5	95	41	2023	6.64	667	<8	<2	3	14	.9	6	<3	68	.16	.133	36	60	1.13	146	.03	<3	2.55	.01	.19	<2	62	<2	2
BL 14+60N	7	106	11	175	2.8	123	40	1829	7.17	1467	<8	<2	3	19	.7	10	<3	76	.26	.122	23	77	1.45	121	.02	<3	2.19	.01	.13	<2	169	2	3
BL 14+50N	4	97	11	160	1.3	142	51	2387	7.71	866	<8	<2	2	19	.5	<3	<3	107	.36	.114	29	103	2.42	131	.03	3	3.14	.01	.13	<2	77	<2	<2
BL 14+40N	2	98	7	237	1.1	178	128	3781	9.13	1241	<8	<2	2	42	.5	20	<3	65	.67	.160	27	48	.82	308	.01	<3	1.57	.01	.12	<2	252	<2	<2
BL 14+30N	2	114	7	175	1.3	113	80	3493	9.08	1160	<8	<2	2	27	.8	9	<3	113	.63	.150	52	55	1.41	226	.01	5	2.54	.01	.14	<2	117	<2	<2
BL 14+20N	8	98	8	205	2.6	172	142	4440	9.86	2558	<8	<2	<2	48	<.5	22	<3	93	.91	.144	32	54	1.08	294	<.01	<3	1.92	.01	.10	<2	806	<2	<2
BL 14+10N	<1	92	13	317	1.8	173	109	4678	11.80	522	<8	<2	<2	23	<.5	88	<3	58	.46	.159	28	24	.26	411	<.01	<3	1.13	<.01	.11	<2	139	<2	<2
BL 14+00N	3	93	19	235	1.7	109	78	3329	8.51	499	<8	<2	2	20	<.5	38	<3	40	.33	.152	20	18	.14	313	<.01	<3	.80	.01	.10	<2	107	<2	<2
BL 13+90N	4	72	9	136	1.6	51	25	1813	4.65	1229	<8	<2	<2	14	.7	3	<3	49	.10	.128	15	32	.54	111	.02	<3	2.24	.01	.08	<2	308	<2	<2
BL 13+80N	8	123	16	198	3.1	108	46	1924	6.34	2253	<8	<2	<2	32	.9	10	<3	25	.42	.110	13	20	.27	96	<.01	<3	1.06	<.01	.09	<2	223	<2	2
L1370 72+50E	3	42	8	129	.3	34	16	2348	3.67	311	<8	<2	<2	15	.6	<3	<3	53	.14	.132	9	45	.63	145	.03	<3	2.72	.01	.08	<2	26	<2	<2
L1370 72+60E	3	52	9	106	.7	31	16	1554	3.43	494	<8	<2	<2	12	.8	<3	<3	35	.12	.244	9	35	.46	94	.02	<3	2.18	.01	.08	<2	68	<2	<2
L1370 72+70E	2	54	18	134	.4	36	22	2705	4.37	582	<8	<2	<2	13	.9	4	<3	50	.10	.137	13	39	.55	145	.02	<3	1.98	.01	.09	<2	61	<2	<2
L1370 72+80E	3	42	9	129	<.3	18	8	1116	3.84	208	<8	<2	<2	22	<.5	3	<3	18	.09	.113	14	10	.16	133	<.01	<3	1.79	.01	.10	<2	20	<2	<2
L1370 72+90E	3	90	14	178	1.3	51	24	2240	5.77	687	<8	<2	2	15	.5	3	<3	46	.09	.163	15	35	.57	133	.01	<3	2.36	.01	.10	<2	41	<2	<2
L1370 73+00E	9	94	7	229	1.3	242	238	4780	7.22	1106	<8	<2	<2	141	.5	12	4	37	3.84	.117	14	20	.43	269	<.01	4	.91	.01	.13	2	71	<2	2
L1370 73+10E	5	151	14	192	3.4	97	54	4454	8.15	922	<8	<2	<2	40	.8	<3	<3	118	.77	.132	125	67	1.67	208	.06	<3	3.25	.01	.41	2	182	<2	2
L1370 73+20E	3	80	9	203	1.1	81	44	2969	7.07	953	<8	<2	<2	27	1.0	3	<3	68	.65	.232	43	35	.71	176	.01	<3	2.03	<.01	.18	2	36	<2	<2
STANDARD DS5/FA-100S	13	146	23	135	.3	25	12	765	3.02	16	<8	<2	3	44	5.7	4	6	60	.72	.095	12	191	.69	137	.09	15	2.00	.04	.14	6	47	47	45

GROUP 1D - 0.50 GM SAMPLE LEACHED WITH 3 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 10 ML, ANALYSED BY ICP-ES.
(>) CONCENTRATION EXCEEDS UPPER LIMITS. SOME MINERALS MAY BE PARTIALLY ATTACKED. REFRACTORY AND GRAPHITIC SAMPLES CAN LIMIT AU SOLUBILITY.
- SAMPLE TYPE: SOIL SS80 60C AU** PT** & PD** GROUP 3B BY FIRE ASSAY & ANALYSIS BY ICP-ES.(TOTAL SAMPLE)
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

Data FA DATE RECEIVED: AUG 16 2004 DATE REPORT MAILED: Sept 2/04



All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of the analysis only.



SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Au**	Pt**	Pd**
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppb	ppb	ppb	
G-1	2	3	5	43	<.3	5	4	566	2.01	<2	<8	<2	3	93	<.5	<3	7	43	.56	.086	8	45	.57	283	.15	<3	1.09	.14	.64	2	<2	<2	<2
L1370 73+30E	3	94	12	117	<.3	90	55	2909	6.92	459	9	<2	<2	18	.8	6	3	147	.47	.174	60	76	2.55	134	.16	3	3.85	.01	.20	<2	13	<2	<2
L1370 73+40E	4	63	6	122	.4	58	28	1894	4.87	280	<8	<2	<2	13	.6	<3	<3	88	.23	.143	20	64	1.42	127	.12	<3	3.24	.01	.15	2	19	<2	<2
L1370 73+50E	4	86	5	153	.5	85	42	2642	5.87	267	9	<2	2	16	.8	6	3	114	.27	.163	24	91	1.82	165	.17	3	3.71	.01	.17	3	27	<2	<2
L1420 71+50E	3	49	8	112	.4	22	13	719	4.15	69	<8	<2	<2	9	<.5	<3	<3	36	.09	.070	11	18	.43	93	.05	3	1.99	.01	.21	<2	8	<2	<2
L1420 71+60E	3	40	5	99	.3	35	13	1241	3.23	51	<8	<2	<2	12	<.5	<3	<3	67	.13	.105	10	69	.85	105	.06	<3	2.75	.01	.07	<2	4	<2	<2
L1420 71+70E	3	54	5	118	.3	42	19	1606	3.73	110	<8	<2	<2	11	<.5	<3	<3	65	.12	.103	13	62	.85	128	.06	<3	2.45	.01	.11	<2	9	<2	<2
L1420 71+80E	4	39	3	134	.3	16	10	605	3.59	83	<8	<2	2	13	<.5	<3	<3	20	.10	.069	16	6	.13	146	<.01	4	1.33	.01	.14	<2	7	<2	<2
L1420 71+90E	5	45	13	141	<.3	17	12	1504	4.04	158	<8	<2	2	36	<.5	4	<3	16	.39	.114	17	4	.11	213	<.01	3	.96	.01	.14	<2	53	19	16
L1420 72+00E	2	43	13	122	.3	26	16	2167	3.86	140	<8	<2	2	10	.6	<3	<3	44	.09	.114	18	26	.43	142	.03	4	1.99	.01	.12	<2	37	<2	<2
L1420 72+10E	3	39	16	117	.4	13	10	1294	3.81	128	9	<2	3	20	.5	<3	4	12	.07	.057	34	<1	.09	281	.01	4	.85	.01	.12	<2	18	<2	<2
L1420 72+20E	3	55	8	123	<.3	44	21	1534	4.10	141	<8	<2	<2	16	<.5	<3	<3	67	.17	.094	13	69	.90	122	.04	<3	2.29	.01	.11	2	38	<2	<2
L1420 72+30E	9	53	19	162	.6	25	15	1752	4.85	146	<8	<2	3	15	<.5	<3	<3	23	.14	.083	22	17	.28	150	.01	<3	1.47	.01	.15	<2	30	<2	<2
L1420 72+40E	17	149	25	206	.6	71	20	831	7.04	225	<8	<2	5	11	.6	5	4	41	.08	.110	37	28	.36	96	.01	4	1.07	.01	.13	<2	43	3	8
L1420 72+50E	30	116	31	199	.7	59	10	514	7.00	175	<8	<2	7	21	<.5	<3	<3	34	.03	.116	34	22	.23	139	.01	7	.90	.01	.17	<2	32	<2	7
L1420 72+60E	49	74	26	191	.6	40	4	196	6.25	44	<8	<2	10	8	<.5	4	<3	25	.01	.085	35	9	.05	91	.01	3	.50	<.01	.16	<2	16	3	7
L1420 72+70E	19	46	24	126	.4	34	11	826	4.60	219	<8	<2	2	8	<.5	<3	<3	42	.03	.102	25	21	.22	118	.01	3	1.02	.01	.16	<2	23	2	3
L1420 72+80E	3	47	12	98	4.6	37	14	967	3.43	1482	<8	<2	<2	22	.5	<3	<3	41	.18	.137	13	29	.41	96	.02	4	2.13	.02	.09	2	185	<2	<2
RE L1420 72+80E	3	48	12	100	4.3	38	14	996	3.49	1524	<8	<2	<2	22	<.5	<3	<3	41	.18	.139	13	29	.40	98	.02	4	2.12	.02	.09	<2	-	-	-
L1420 72+90E	4	180	20	243	24.0	315	99	3742	9.14	8137	<8	<2	2	46	.5	44	<3	37	.62	.167	27	23	.53	130	.01	<3	1.25	.01	.08	3	1524	<2	<2
L1420 73+10E	10	155	18	191	.7	81	27	1588	5.01	639	<8	<2	3	13	1.2	16	<3	19	.06	.049	10	7	.13	174	<.01	5	.72	<.01	.16	<2	70	<2	4
L1420 73+20E	9	132	23	187	1.1	75	36	1793	5.91	739	<8	<2	5	23	1.0	5	<3	61	.12	.116	27	36	.83	227	.06	<3	1.96	.02	.22	<2	69	<2	2
L1420 73+30E	8	115	25	197	1.5	77	36	2110	6.13	813	<8	<2	3	19	1.0	8	<3	72	.18	.151	27	44	.99	160	.06	<3	2.39	.01	.23	2	68	<2	2
L1420 73+40E	6	167	34	193	.7	107	45	7340	7.31	616	<8	<2	2	39	.7	13	<3	103	.40	.161	38	56	1.19	331	.04	<3	2.36	.01	.22	<2	55	2	5
L1420 73+50E	8	134	28	211	.3	121	53	11469	7.51	365	<8	<2	2	50	1.0	7	<3	92	.53	.184	37	44	.94	498	.03	<3	2.13	.01	.21	<2	28	<2	5
L1470 71+50E	3	32	9	74	.3	25	9	649	3.21	89	<8	<2	<2	8	<.5	<3	<3	60	.07	.079	11	45	.59	73	.04	<3	2.33	.01	.06	<2	10	<2	<2
L1470 71+60E	5	40	11	104	.4	29	13	916	3.37	63	<8	<2	<2	8	<.5	<3	<3	61	.08	.110	12	41	.65	79	.05	<3	2.52	.01	.10	<2	11	<2	<2
L1470 71+70E	6	110	13	177	.3	82	38	1773	5.31	151	<8	<2	3	12	.7	3	4	56	.07	.112	24	43	.98	121	.03	<3	2.16	.01	.21	<2	18	<2	4
L1470 71+80E	6	120	14	162	.4	68	31	1355	5.17	176	<8	<2	5	13	.7	<3	<3	49	.08	.104	30	33	.73	112	.03	<3	1.66	.01	.22	<2	41	3	7
L1470 71+90E	6	92	20	169	.3	67	23	1683	4.91	89	<8	<2	2	16	.5	<3	<3	55	.07	.130	22	39	.59	149	.01	<3	2.46	.01	.18	<2	8	<2	<2
L1470 72+00E	6	134	22	197	<.3	76	26	1832	5.33	152	<8	<2	<2	33	.5	<3	<3	58	.20	.206	33	40	.79	148	.02	<3	2.18	.01	.21	<2	50	48	43
L1470 72+10E	5	67	21	142	.6	49	19	1271	4.10	76	<8	<2	<2	24	.5	<3	<3	55	.19	.140	20	34	.47	183	.03	3	2.06	.01	.14	<2	12	<2	2
L1470 72+20E	3	81	18	150	<.3	51	19	3067	3.98	64	<8	<2	<2	28	.7	<3	<3	59	.32	.159	17	41	.89	189	.06	<3	2.43	.01	.19	2	16	<2	5
L1470 72+30E	11	84	23	150	.6	47	23	1407	4.53	80	<8	<2	3	16	.9	3	<3	44	.18	.122	21	30	.56	130	.03	4	1.42	.01	.20	<2	15	3	10
L1470 72+40E	9	121	17	234	.4	105	43	2885	6.03	184	<8	<2	4	17	.7	<3	<3	67	.16	.174	26	47	.93	189	.02	<3	2.34	.01	.18	2	28	2	5
STANDARD DS5/FA-100S	13	146	25	140	.4	25	12	767	3.04	19	8	<2	3	46	5.6	3	5	61	.76	.097	13	189	.70	136	.10	16	2.07	.04	.15	5	50	48	50

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.



SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Au**	Pt**	Pd**
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	%	ppm	ppm	%	ppm	%	%	%	%	%	ppm	ppb	ppb	ppb
G-1	2	2	4	41	<.3	5	4	558	1.97	<2	<8	<2	4	85	<.5	<3	<3	42	.55	.081	8	47	.59	278	.15	<3	1.05	.12	.57	<2	<2	<2	<2
L1470 72+50E	4	78	15	161	<.3	54	30	2883	4.65	305	<8	<2	<2	12	<.5	<3	<3	68	.12	.170	17	53	.89	137	.05	<3	2.44	.01	.15	<2	40	<2	<2
L1470 72+60E	3	150	11	168	4.0	142	51	2948	8.37	1933	<8	<2	3	26	<.5	10	3	26	1.02	.157	24	18	.21	114	<.01	<3	.78	.01	.09	<2	811	<2	5
L1470 72+70E	4	93	8	161	16.2	269	105	3763	11.51	>10000	<8	2	<2	73	<.5	32	6	34	1.08	.229	22	35	.30	178	<.01	<3	.98	<.01	.08	<2	2833	<2	3
L1470 72+80E	4	35	10	65	.6	33	10	538	3.48	876	<8	<2	<2	12	<.5	<3	<3	49	.18	.091	10	25	.36	101	.02	5	1.44	.01	.05	<2	85	<2	<2
L1470 72+90E	5	56	12	102	.7	39	14	712	4.21	663	<8	<2	<2	8	<.5	<3	<3	54	.07	.128	14	45	.64	107	.02	<3	1.94	.01	.10	<2	69	<2	<2
L1470 73+10E	6	119	24	154	1.2	96	38	2257	6.35	817	<8	<2	2	16	<.5	6	<3	80	.29	.125	61	66	1.47	133	.04	<3	2.57	.01	.16	<2	80	<2	3
L1470 73+20E	4	100	9	200	.3	142	82	2457	8.52	716	10	<2	2	23	<.5	17	<3	87	.48	.146	30	58	1.07	165	.01	<3	1.85	.01	.13	<2	74	<2	<2
L1470 73+30E	5	89	16	168	.5	88	39	1474	6.88	786	<8	<2	3	18	<.5	7	5	80	.28	.134	28	55	1.09	131	.03	<3	2.11	.01	.16	<2	130	<2	2
L1470 73+40E	5	98	11	160	.7	81	35	1372	6.02	1028	<8	<2	2	16	<.5	8	3	63	.19	.102	21	44	.80	121	.03	<3	1.60	.01	.15	<2	224	<2	<2
L1470 73+50E	7	121	25	169	.4	77	32	2021	5.49	541	9	<2	2	23	.5	3	<3	71	.29	.119	29	52	1.05	149	.07	<3	2.14	.01	.23	<2	114	<2	4
L1520 71+50E	3	156	9	134	<.3	149	44	1147	5.88	298	<8	<2	<2	13	<.5	<3	<3	121	.33	.060	7	172	1.66	148	.09	5	3.72	.01	.11	<2	51	<2	<2
L1520 71+60E	4	237	5	210	<.3	261	92	3853	7.97	128	<8	<2	<2	15	1.0	<3	<3	140	.36	.086	17	379	2.44	362	.23	<3	4.42	.01	.43	2	16	2	3
L1520 71+70E	3	88	12	107	<.3	80	27	1659	4.40	84	<8	<2	<2	12	<.5	<3	<3	88	.20	.134	11	84	1.31	110	.14	<3	2.83	.01	.13	<2	12	<2	<2
L1520 71+80E	2	74	14	129	<.3	60	22	1730	4.19	73	<8	<2	<2	10	<.5	<3	<3	78	.12	.127	12	72	1.12	117	.11	<3	3.13	.01	.11	<2	14	<2	<2
L1520 71+90E	4	66	11	139	<.3	63	19	1924	3.98	96	<8	<2	<2	14	<.5	<3	<3	68	.20	.140	12	77	.97	246	.05	<3	2.25	.01	.11	<2	11	<2	<2
L1520 72+00E	6	158	12	141	<.3	136	44	2864	5.86	147	<8	<2	2	13	<.5	<3	<3	102	.25	.097	15	138	1.92	171	.10	5	3.14	.01	.20	<2	15	<2	3
L1520 72+10E	3	77	10	139	<.3	66	27	2787	4.03	85	<8	<2	<2	23	<.5	<3	<3	70	.54	.126	10	75	1.02	198	.06	<3	2.28	.01	.14	<2	8	<2	<2
L1520 72+20E	7	208	14	218	1.8	97	40	1857	6.72	1400	11	<2	4	11	.8	<3	<3	49	.20	.083	25	25	.44	160	<.01	<3	1.47	.01	.13	<2	348	<2	2
L1520 72+30E	4	92	10	124	2.2	51	29	2162	5.07	1940	<8	<2	<2	19	<.5	4	<3	44	.36	.169	12	39	.50	192	.01	<3	1.55	.01	.09	<2	265	<2	<2
L1520 72+40E	5	83	10	116	.5	42	18	1068	4.81	783	<8	<2	<2	6	<.5	<3	<3	59	.05	.129	15	48	.61	107	.01	<3	2.28	.01	.08	<2	183	<2	<2
L1520 72+50E	3	163	3	132	1.7	67	49	2115	8.17	1915	<8	<2	<2	15	<.5	4	<3	112	.37	.097	15	43	1.19	166	.01	<3	2.59	.01	.09	<2	229	<2	<2
L1520 72+60E	3	141	11	154	12.3	84	55	2621	8.41	5407	<8	<2	2	21	.5	12	5	67	.40	.115	18	31	.74	169	.01	<3	1.51	.01	.11	2	1063	<2	<2
L1520 72+70E	6	165	22	223	12.3	139	63	3564	8.97	7654	<8	<2	2	54	5.2	17	<3	26	.50	.137	28	25	.28	103	.01	<3	.82	.01	.09	2	1378	<2	<2
L1520 72+78E	4	101	8	156	4.4	69	25	1201	6.13	2028	<8	<2	<2	22	<.5	6	4	65	.30	.133	17	53	.81	127	.02	<3	2.16	.01	.15	<2	312	<2	<2
RE L1520 72+78E	5	99	9	155	4.2	69	24	1187	6.04	1983	<8	<2	<2	22	<.5	4	3	64	.30	.132	17	51	.81	126	.02	<3	2.12	.01	.15	<2	-	-	-
L1520 72+90E	5	91	13	152	.8	66	27	1815	5.28	753	<8	<2	<2	19	.6	5	3	64	.38	.124	25	53	.88	129	.04	<3	2.09	.01	.15	<2	75	<2	<2
L1520 73+10E	4	96	8	166	2.6	86	29	1115	6.42	1996	<8	<2	<2	18	<.5	10	<3	64	.30	.144	29	49	.83	121	.03	<3	2.02	.01	.14	<2	466	<2	<2
L1520 73+20E	3	96	11	167	5.5	81	28	1092	6.38	2838	<8	<2	2	23	<.5	7	4	58	.30	.139	23	48	.81	116	.03	<3	1.90	.01	.14	2	638	<2	<2
L1520 73+30E	5	98	17	167	2.1	76	31	1450	5.94	1102	<8	<2	2	23	<.5	5	4	67	.36	.137	27	55	1.03	126	.04	<3	2.19	.01	.18	<2	205	<2	2
L1520 73+40E	4	167	13	172	4.3	132	46	2182	6.81	483	<8	<2	2	34	.5	5	3	93	.53	.087	23	177	1.64	123	.10	<3	2.63	.01	.35	<2	102	<2	5
L1520 73+50E	4	97	9	171	<.3	89	48	2812	7.27	152	<8	<2	<2	45	<.5	<3	<3	114	.77	.109	44	68	2.01	169	.15	<3	3.79	.01	.30	<2	10	<2	<2
L1570 71+50E	4	35	16	61	<.3	22	10	1886	2.92	46	<8	<2	<2	11	<.5	<3	<3	49	.11	.106	9	28	.27	75	.04	<3	1.66	.01	.08	<2	8	<2	<2
L1570 71+60E	4	105	12	170	<.3	76	32	4788	5.00	35	<8	<2	<2	34	1.2	<3	3	60	.66	.253	18	39	.46	315	.01	<3	1.66	.01	.21	<2	17	<2	<2
L1570 71+70E	10	183	18	240	<.3	100	38	4309	6.26	37	<8	<2	2	27	.5	<3	<3	68	.31	.141	33	39	.56	189	.02	<3	2.08	.01	.24	<2	34	<2	<2
STANDARD DS5/FA-100S	13	146	25	137	<.3	25	12	756	3.03	18	<8	<2	3	46	5.6	3	6	60	.74	.094	13	193	.69	136	.10	16	2.03	.04	.14	4	50	48	48

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.



SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Au**	Pt**	Pd**
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppb	ppb	ppb	
G-1	1	4	<3	45	<.3	5	4	557	1.95	<2	<8	<2	3	81	<.5	<3	<3	41	.53	.080	7	44	.57	261	.14	<3	1.00	.10	.55	3	<2	<2	<2
L1570 71+80E	5	229	26	252	.4	71	18	2159	5.89	19	<8	<2	2	24	.6	<3	<3	40	.20	.116	14	20	.18	118	.01	<3	.96	<.01	.18	<2	13	2	2
L1570 71+90E	4	148	22	173	.3	47	23	2112	5.03	33	<8	<2	2	27	<.5	<3	<3	41	.29	.134	14	20	.29	169	.01	<3	1.53	.01	.17	<2	5	<2	2
L1570 72+00E	7	140	15	252	<.3	75	30	2962	5.95	65	12	<2	<2	18	1.2	<3	<3	60	.18	.115	30	37	.61	144	.06	<3	2.29	.01	.29	<2	3	<2	2
L1570 72+10E	4	129	9	192	<.3	74	22	1120	6.52	118	<8	<2	3	13	<.5	<3	<3	66	.20	.095	15	37	.76	144	<.01	<3	1.87	<.01	.14	<2	6	<2	<2
L1570 72+20E	1	58	14	187	<.3	52	23	3953	4.02	37	10	<2	<2	30	1.0	<3	<3	62	.62	.152	15	51	.81	461	.08	<3	2.41	.01	.15	<2	<2	<2	<2
L1570 72+30E	6	183	27	293	<.3	118	34	2059	5.92	89	<8	<2	4	18	.7	3	<3	72	.18	.122	31	51	.64	255	.01	<3	2.21	.01	.19	<2	4	<2	<2
L1570 72+40E	15	193	25	334	<.3	120	45	3092	6.88	25	10	<2	4	18	2.9	5	<3	79	.34	.205	58	65	1.26	189	.01	<3	2.30	<.01	.27	2	<2	3	5
L1570 72+50E	7	145	18	237	2.7	104	36	2614	7.10	605	<8	<2	3	20	.8	10	<3	64	.35	.145	24	43	.55	154	.01	<3	1.79	.01	.13	2	57	<2	<2
L1570 72+60E	5	117	15	205	1.0	80	49	5300	6.19	558	<8	<2	<2	39	1.2	5	<3	71	.59	.189	31	41	.74	273	.03	<3	1.99	.01	.18	3	42	<2	<2
L1570 72+70E	5	121	18	316	.5	90	41	2711	6.55	625	10	<2	2	31	1.2	7	<3	72	.44	.204	24	41	.67	317	.02	<3	2.20	.01	.16	2	32	<2	<2
L1570 72+80E	12	168	24	286	1.1	110	47	3375	7.27	1186	<8	<2	3	27	1.5	12	<3	61	.25	.172	28	41	.57	266	.01	<3	1.95	.01	.19	2	688	2	3
L1570 72+90E	17	274	27	384	3.8	172	67	3051	10.35	1277	10	<2	4	30	.5	10	<3	53	.42	.078	38	38	.68	161	.01	<3	1.71	.01	.11	<2	834	2	11
L1570 73+10E	6	137	5	165	<.3	113	34	1513	6.07	550	<8	<2	<2	19	<.5	6	<3	81	.45	.099	17	74	1.06	217	.04	<3	3.25	.01	.08	<2	165	<2	<2
L1570 73+20E	4	92	10	168	.3	80	25	1650	4.97	245	<8	<2	<2	13	<.5	4	<3	76	.16	.113	17	63	.99	159	.05	<3	3.05	.01	.09	<2	47	<2	<2
L1570 73+30E	8	149	11	220	1.5	124	43	2751	6.86	559	<8	<2	3	10	.6	12	<3	37	.05	.114	18	26	.19	144	<.01	<3	1.44	<.01	.11	2	39	<2	3
L1570 73+40E	8	204	24	209	.8	108	28	2718	6.72	425	<8	<2	3	25	.5	7	<3	80	.17	.107	23	46	.69	102	.01	<3	2.03	.01	.11	<2	121	<2	3
RE L1570 73+40E	9	206	22	206	.8	109	28	2737	6.79	425	<8	<2	3	26	.7	9	<3	81	.17	.109	24	46	.71	104	.01	<3	2.05	.01	.11	<2	<2	<2	<2
L1570 73+50E	9	159	9	306	.3	92	21	840	5.58	177	<8	<2	3	11	.9	5	<3	58	.07	.086	22	44	.61	232	.01	<3	2.19	<.01	.12	<2	29	<2	<2
L1620 71+50E	4	62	12	148	<.3	51	31	2512	4.66	45	<8	<2	<2	35	.7	3	<3	90	.66	.148	14	61	1.24	257	.10	<3	2.57	.01	.24	<2	2	<2	<2
L1620 71+60E	1	69	8	121	<.3	47	23	2573	3.96	44	<8	<2	<2	35	.6	<3	<3	71	.73	.176	14	48	.95	225	.06	<3	2.27	.01	.17	<2	<2	<2	<2
L1620 71+70E	<1	149	3	148	<.3	89	45	2815	6.12	61	9	<2	<2	24	.7	3	<3	114	.91	.114	11	152	2.19	245	.17	<3	3.39	.01	.41	2	2	<2	<2
L1620 71+80E	1	108	9	134	<.3	89	35	1308	5.56	42	<8	<2	<2	19	<.5	<3	<3	103	.56	.093	10	113	2.03	142	.21	<3	3.90	.01	.17	2	<2	<2	<2
L1620 71+90E	2	99	14	166	<.3	77	41	4080	5.60	107	<8	<2	<2	22	1.0	5	<3	87	.71	.155	31	73	1.44	229	.08	<3	2.80	.01	.28	<2	4	<2	<2
L1620 72+00E	4	88	22	153	.3	45	33	3343	4.53	133	8	<2	<2	34	.9	<3	<3	49	.89	.221	17	33	.61	211	.02	5	1.54	.01	.23	<2	<2	<2	<2
L1620 72+10E	3	96	8	194	.3	56	29	1484	6.32	78	<8	<2	3	12	.6	3	<3	78	.19	.135	15	57	1.14	149	.02	<3	3.22	.01	.16	<2	3	<2	<2
L1620 72+20E	6	87	15	139	.3	49	25	2289	5.14	175	<8	<2	<2	10	<.5	3	<3	73	.08	.108	19	55	.92	170	.03	<3	2.85	.01	.12	<2	12	<2	2
L1620 72+30E	2	64	11	102	<.3	37	14	1086	3.87	72	<8	<2	<2	9	<.5	<3	<3	61	.08	.096	14	49	.75	116	.03	<3	2.26	.01	.10	<2	13	<2	2
L1620 72+40E	3	119	10	165	<.3	72	29	2323	6.26	69	8	<2	<2	12	.5	5	<3	78	.17	.076	23	57	1.29	174	.07	<3	2.65	.01	.22	<2	12	<2	<2
L1620 72+50E	1	69	12	154	<.3	43	26	2051	4.31	64	<8	<2	<2	9	.5	<3	<3	68	.10	.137	16	52	.88	132	.05	<3	2.74	.01	.12	<2	7	<2	<2
L1620 72+60E	9	168	18	233	1.1	110	50	3289	7.55	388	<8	<2	2	19	1.0	5	<3	71	.37	.133	33	57	1.18	154	.03	<3	2.29	.01	.19	<2	45	2	3
L1620 72+70E	4	79	11	142	.7	63	23	1303	4.99	131	<8	<2	<2	10	.5	3	<3	74	.14	.098	13	64	1.18	152	.04	<3	2.81	.01	.11	<2	11	<2	<2
L1620 72+80E	3	86	15	198	.6	70	25	1214	5.28	250	<8	<2	<2	16	.7	5	<3	67	.24	.159	16	48	.90	169	.02	<3	2.56	<.01	.09	<2	8	<2	<2
L1620 72+90E	6	140	9	224	.5	97	33	1114	6.78	384	<8	<2	3	12	.8	6	<3	78	.15	.126	23	55	1.09	99	.02	<3	2.51	.01	.13	<2	32	<2	4
L1620 73+10E	2	39	8	94	.3	32	16	2562	3.30	72	<8	<2	<2	10	<.5	<3	<3	62	.11	.093	12	36	.59	168	.04	3	2.04	.01	.09	<2	8	<2	<2
STANDARD DS5/FA-100S	12	144	26	134	.5	25	12	753	3.00	18	<8	<2	3	44	5.3	4	7	58	.72	.091	13	190	.68	136	.09	18	1.99	.04	.14	6	48	50	47

Sample type: SOIL SS80 60C. Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.



SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Au*	Pt**	Pd**
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppb	ppb	ppb	
G-1	1	3	<3	42	<.3	5	4	539	1.95	<2	<8	<2	4	84	<.5	<3	<3	40	.53	.080	7	52	.57	261	.14	6	1.01	.10	.54	<2	<2	<2	<2
L1620 73+20E	8	130	13	176	2.5	82	30	1054	5.53	905	<8	<2	4	6	<.5	13	3	31	.05	.061	22	24	.36	106	.01	3	1.38	.01	.09	2	288	<2	<2
L1620 73+30E	2	55	10	134	<.3	50	24	6050	3.93	81	<8	<2	<2	31	.9	<3	4	60	.38	.190	16	57	.75	370	.03	3	2.41	.01	.10	2	27	<2	<2
L1620 73+40E	4	76	<3	149	<.3	66	22	1161	4.94	187	<8	<2	<2	18	.5	3	4	72	.23	.131	13	56	1.02	263	.03	<3	2.39	.01	.10	<2	29	<2	<2
L1620 73+50E	11	161	19	259	<.3	101	29	1641	7.76	249	<8	<2	3	5	<.5	15	8	45	.03	.155	19	23	.24	155	<.01	3	1.33	<.01	.11	2	36	<2	<2
STANDARD DS5/FA-100S	12	148	26	133	.3	25	13	741	2.99	18	<8	<2	3	46	5.4	3	6	58	.73	.094	13	188	.68	137	.10	18	1.99	.04	.14	6	49	49	47

Sample type: SOIL SS80 60C.

Appendix D


Author's Statement of Qualifications

Statement of Qualifications

I, David St. Clair Dunn, Professional Geoscientist, with a business address of 1154 Marine Drive, Gibsons, B.C., Canada, certify that:

1. I am a graduate of the University of British Columbia, Vancouver, B.C. and hold a degree of Bachelor of Science in Geology.
2. I have practiced my profession as a prospector and geologist for 35 years.
3. I am registered as a Professional Geoscientist with the Association of Professional Engineers and Geoscientists of the Province of British Columbia (Reg. # 18,479). I am a Fellow of the Geological Association of Canada and a member of the Association of Exploration Geochemists, the Canadian Institute of Mining, Metallurgy and Petroleum, the Honorary Advisory Board to the B.C. and Yukon Chamber of Mines, the Society of Economic Geologists and the Mining Exploration Group. I am the qualified persons for the purposes of National Instrument 43-101 in reference to this report.
4. I directly supervised the 2004 geochemical surveying and trenching programs on the Aumax Property.
5. I am the sole author of this report.
6. I am not aware of any material fact or material change from the information in this report that would make the report misleading.
7. I consent to the use of this report for the purpose of a private or public financing.

Signed:



A circular professional seal for a geoscientist in the Province of British Columbia. The seal contains the text: "PROFESSIONAL", "PROVINCE OF", "D. S. C. DUNN", "BRITISH COLUMBIA", and "GEOSCIENTIST". A handwritten signature is written across the seal.