

2006 TECHNICAL REPORT
DIAMOND DRILLING, REVERSE CIRCULATION DRILLING AND
BEDROCK TRENCHING

LUSTDUST PROPERTY

OMINECA MINING DIVISION,
BRITISH COLUMBIA, CANADA

(93N / 11W)

FOR

ALPHA GOLD CORP.
410 DONALD STREET
COQUITLAM, B.C.
V3K 3Z8

BY

DARYL J. HANSON, P.ENG.
IN-DEPTH GEOLOGICAL SERVICES

APRIL 28, 2007

TABLE OF CONTENTS

	Page
1. SUMMARY	1
2. INTRODUCTION AND TERMS OF REFERENCE	4
3. DISCLAIMER	4
4. PROPERTY DESCRIPTION AND LOCATION	5
5. ACCESSIBILITY, CLIMATE, LOCAL RESOURCES, INFRASTRUCTURE AND PHYSIOGRAPHY	6
6. HISTORY	6
7. GEOLOGICAL SETTING	8
7.1 Regional Geology	8
7.2 Lustdust Property Geology Summary	9
7.3 Supracrustal Rocks	10
7.4 Intrusive Rocks	11
7.5 Structure	13
8. DEPOSIT TYPES	14
9. MINERALIZATION	17
9.1 General	17
9.2 Zn-Pb-As-Sb Vein Zone: Number 1 Zone	17
9.3 Zn-Pb-Ag-Au CRD Mineralization: Number 2, 3, 4b, and East Zones	18
9.4 Canyon Creek Skarn	19
10. 2006 EXPLORATION PROGRAM	21
11. DIAMOND DRILLING PROGRAM	21
11.1 Core Sampling Procedures	23
11.2 Core Sample Analyses and Results	23
11.3 Data Verification and Results	23
11.4 Reclamation	24
11.5 Diamond Drilling Results: Canyon Creek Skarn Zone	26
11.6 Diamond Drilling Results: GD Zone	27
11.7 Diamond Drilling Results: Number 4B Zone	28
11.8 Diamond Drilling Results: Valley Zone	28

	page
12. REVERSE CIRCULATION DRILLING	29
12.1 Chip Sampling Procedure	29
12.2 Chip Sample Analyses and Results	30
12.3 Data Verification	30
12.4 Data Verification	31
12.5 Reverse Circulation Drilling Results	32
13. BEDROCK TRENCHING	33
13.1 Sampling Procedures	33
13.2 Sample Analyses and Results	33
13.3 Data Verification	33
13.4 Reclamation	34
13.5 Bedrock Trenching Results	35
14. INTERPRETATION AND CONCLUSIONS	36
15. RECOMMENDATIONS	37
16. 2006 EXPLORATION PROGRAM EXPENDITURES	39
17. REFERENCES	40
18. CERTIFICATE OF AUTHOR	43

<u>LIST OF FIGURES</u>		page
Figure 1.	Lustdust Project Location Map, B.C. Canada	after 5
Figure 2.	Alpha Gold Claim Holdings, Lustdust Project	after 6
Figure 3.	Regional Geology Map of the Lustdust Property Showing Major Intrusions and Terranes	after 8
Figure 4.	Generalized Geology Compilation Map of the Lustdust Property	after 9
Figure 5.	2006 Drill-hole Location Map Canyon Creek Skarn, GD, and 4B Zones	after 21
Figure 6.	2006 Drill-hole Location Map Valley Zone	after 29
Figure 7.	2006 Bedrock Trenching Location Map	after 33

LIST OF TABLES

Table 1.	Lustdust Claim Information	5
Table 2.	Exploration History Synopsis	7
Table 3.	2006 Diamond Drill Hole Summary Data	22
Table 4.	Summary of 2006 Diamond Drill-hole Results	25
Table 5.	2006 RC Drill-hole Summary Data	30
Table 6.	Summary of 2006 RC Drill-hole Results	31
Table 7.	2006 Bedrock Trenching Summary Data	33
Table 8.	Summary of 2006 Bedrock Trenching Results	34

LIST OF APPENDICES

- Appendix I 2006 Diamond Drill-hole Logs**
- Appendix II 2006 Reverse Circulation Drill-hole Logs**
- Appendix III 2006 Bedrock Trenching Assay Logs**
- Appendix IV ALS Chemex Analytical Technique**
- Appendix V CDN Resource Laboratories Ltd. - Standard CDN-CGS-7,
Standard CDN-CGS-10 and Blank CDN-BL2**
- Appendix VI 2006 Diamond Drilling - Certificates of Analysis**
- Appendix VII 2006 Reverse Circulation Drilling - Certificates of Analysis**
- Appendix VIII 2006 Bedrock Trenching - Certificates of Analysis**

1. SUMMARY

The Lustdust property consists of 17 contiguous "cell" claims which are 100% owned by Alpha Gold Corp. and cover an area of 8,561 ha in north-central British Columbia. The claims are mainly underlain by Cache Creek Assemblage sedimentary and volcanic rocks which lie immediately west of the Pinchi Fault, a major regional and terrane bounding fault. Supracrustal rocks are cut by Eocene intrusive bodies ranging widely in composition from calc-alkaline diorite to monzonite to sub-alkalic rhyodacite (Ray et al., 2002).

Mineralization is hosted within a folded, upright to locally overturned, east-verging sequence of steeply west-dipping, northwest-striking limestones, mafic tuffs and siliceous phyllites. Gold, copper, zinc and silver mineralization occurs in several forms, all of which are related to an Eocene hydrothermal system. Predominant styles of mineralization targeted by the 2006 exploration program include:

1. **Carbonate hosted, Au-Ag-Zn massive sulphide mantos**
2. **Cu-Au-Ag skarns**
3. **Sediment hosted Au**

The entire hydrothermal system, except for molybdenum rich veins and stockworks in the Glover Stock, is auriferous with 0.5 to >1 g/t gold values common throughout. Bonanza gold grades of >30 g/t Au over 1 to 9.7 m widths have been cored and may be associated with massive sulphide replacement bodies. The system is strongly zoned over at least 3000 m laterally and shows polyphase intrusive and mineralization characteristics typical of major Au-Cu-Zn-Pb-Ag skarn replacement systems found throughout the northern and southern cordillera.

Alpha Gold's 2006 exploration program was directed towards:

1. Fill-in exploration diamond drilling of the Canyon Creek Skarn (CCS) including the highly favorable footwall zone.
2. Diamond drilling and trenching coincident arsenic-zinc soil geochemistry anomalies over the favorable limestone unit along strike to the north of the Number 3 Manto oxide zone.
3. Refining the geologic base-map of the property.
4. Diamond drilling a gold-arsenic soil geochemistry anomaly west of the Number 4b Zone.
5. Evaluating the sediment-hosted gold potential of a large area centered on the historic Takla-Bralorne Mercury Mine by reverse circulation and follow-up diamond drilling.

Thirty two (32) NQ diamond drill holes were completed in two phases of drilling between June 12 and December 5, 2006 totaling 6,855.1 metres. Twenty four (24) reverse circulation rotary/percussion holes were drilled between July 22 and August 29 for a total of 3,054.1 metres. Three (3) trenches were excavated to bedrock over a total length of

one hundred sixty nine metres. Two thousand nine hundred five (2 905) samples including 31 duplicates, 39 blanks and 40 standards were submitted for analysis. Total cost for the 2006 program was \$1,183,990.

Highlights of the 2006 program are as follows:

1. Trenching and diamond drilling a coincident gold-arsenic soil geochemistry anomaly north of the Number 3 Zone resulted in the discovery of the GD Zone. The trenches uncovered sulphide and oxide mineralization across significant widths over a strike length of 100 metres. The zone remains open to the north.
 - Trench LTR06-01 returned **5.176 g/t gold, 18.9 g/t silver, and 3.08% zinc over 4.5 metres of red oxide.**
 - Trench LTR06-02 uncovered **24.0 metres of red oxide and 2.8 metres of massive arsenopyrite and sphalerite.** The oxide averaged **1.99 g/t gold, 39.0 g/t silver and 1.83% zinc over 8.0 metres.** The massive sulphide returned **5.642 g/t gold, 32.1 g/t silver and 4.29% zinc across 2.8 metres.**
 - A grab sample of oxide from trench LTR06-02 assayed **22.3% lead and 2,210 g/t silver.**
 - Trench LTR06-03 returned **2.054 g/t gold, 26.4 g/t silver, and 2.11% zinc over 10.3 metres of red oxide.**
 - Diamond drill-hole LD06-23 returned **0.375 g/t gold, 9.2 g/t silver and 2.436% zinc over 11.2 metres from 9.1 to 20.3 metres.**
2. Drilling in the CCS Zone continued to intersect high grade gold-copper mineralization particularly at the hanging-wall and foot-wall of the zone.
 - Drill-hole LD06-05 returned **1.099 g/t Au, 23.5 g/t Ag, 0.67% Cu, 0.29% Zn over 14.1m from 113.0 to 127.1 metres including 1.960 g/t Au, 43.5 g/t Ag, 1.20% Cu, 0.55% Zn over 6.5m from 113.0 to 119.5 metres.**
 - Drill-hole LD06-06 returned **0.631 g/t Au, 14.2 g/t Ag , 0.72% Cu over 15.2m from 145.4 to 160.6 metres.**
 - Drill-hole LD06-07 returned **2.502 g/t Au, 64.1 g/t Ag, 2.45% Cu, 2.88% Zn over 4.9m from 110.8 to 115.7 metres; and 1.523 g/t Au, 33.2 g/t Ag,, 0.98% Cu over 10.1m from 136.3 to 146.4 metres.**
 - Drill-hole LD06-08 returned **0.942 g/t Au, 46.7 g/t Ag, 1.55% Cu , 0.11% Zn over 1.6m from and 108.7 to 110.3 metres; and 4.765 g/t Au, 174.6 g/t Ag, 4.71% Cu, 0.10% Zn over 2.1 metres from 152.1 to 154.2 metres.**

- Drill-hole LD06-12 intersected **1.450 g/t Au, 27.7 g/t Ag, 1.81% Cu over 19.7m from 187.6 to 207.3 metres**. This significant intersection includes **11.3 metres grading 1.703 g/t Au, 36.1 g/t Ag, 2.41% Cu from 190.1 to 201.4 metres**.
 - Drill-hole LD06-15 returned **0.918 g/t gold, 11.8 g/t silver, and 0.796% copper over 6.9 metres from 282.1 to 289.0 metres**.
 - Drill-hole LD06-16 returned **0.873 g/t gold, 13.5 g/t silver and 2.124% copper over 18.7 metres from 344.4 to 363.1 metres**.
 - Drill-hole LD06-17 returned three intersections totalling **1.861 g/t gold, 23.9 g/t silver and 2.309% copper over 9.5 metres between 422.2 and 457.7 metres**.
 - Drill-hole LD06-18 returned **1.984 g/t gold, 46.9 g/t silver and 2.172% copper over 13.8 metres from 347.9 to 361.7 metres**.
3. The 2006 reverse circulation and follow-up diamond drilling program to evaluate the sediment hosted gold potential in the limestone and argillite surrounding the historic Takla-Bralorne Mercury Mine resulted in the discovery of the Valley Zone. The lack of sulfide mineralization, the host rock and mercury trace element association, and the spatial relationship with the skarn and manto mineralization, are all indicators of the potential to discover a sediment-hosted gold deposit in this area.
- Reverse circulation rotary hole LRC06-23 returned **11.02 g/t gold over 7.6 metres from 68.6 to 76.2 metres including 46.9 g/t over 1.5 metres**.
 - Follow-up diamond drill-hole LD06-31 returned **anomalous gold values over 21.3 metres from 89.0 to 110.3 metres and over 9.1 metres from 192.6 to 201.7 metres including 2.6 g/t over 1.5 metres** in unaltered limestone without visible mineralization.
 - Follow-up diamond drill-hole LD06-32 returned **anomalous gold values over 7.6 metres from 121.0 to 128.6 including 1.865 g/t over 1.5 metres** in unaltered limestone without visible mineralization.

As in the preceding seasons, particularly since 1996, positive exploration results continue to emerge on this property. The styles, grades and distribution of the mineralization observed support the model linking porphyry, skarn, manto, vein and sediment hosted gold that was proposed by Sillitoe and Bonham in 1990. A continuing program of aggressive diamond drilling is recommended for 2007 to test the sediment hosted gold potential surrounding LD06-31. Additionally, an integrated program of geophysics, geochemistry, mapping and prospecting is recommended as an initial exploration phase for the newly acquired ground south of the Valley Zone.

2. INTRODUCTION AND TERMS OF REFERENCE

This report has been commissioned by the management of Alpha Gold Corp. The report documents all the results from the 2006 diamond drilling, reverse circulation drilling and bedrock trenching programs and outlines all significant changes to the geological database. The report is based on an extensive review and compilation of private corporate reports and documents as well as publicly available geological and scientific papers.

The report is also based on the author's personal knowledge of the property obtained during the period from June 12 to December 5, 2006. During this time, the author designed and supervised the drill programs, including access construction and reclamation. The author also logged the core and supervised the core and chip sampling. All work was done according to accepted "best practices" for the industry.

3. DISCLAIMER

Implementation of the 2006 exploration program and the writing of this report have relied upon an abundance of excellent previous work. The surface geological map developed by several individuals, most particularly by Dr. Gerry Ray and his co-workers (Ray et al., 2002), has been extensively utilized. The author has also relied on many of the previous geological reports on this property, particularly the work of Evans (1996, 1997); Megaw (1999, 2000, and 2001), Oliver (2002, 2003) and Hanson (2004, 2005).

On a property with an abundance of historical drilling, conducted over a 60-year period, it would be surprising if all drill collars have been identified. Although a substantive effort has been made to accurately locate, identify, and survey historical drill collars, not all of these have been identified and not all historical drill results, or the results of other technical surveys, are available.

4. PROPERTY DESCRIPTION AND LOCATION


The Lustdust Property is located in the Omineca Mining Division of north-central British Columbia on NTS 93N/11W at latitude 55 34' North (Northing 6160175) and 125 25' West (Easting 347850), UTM Zone 10, NAD 83 (Figure 1).

Pursuant to agreements made July 15, 1989 and February 21, 1992, Alpha Gold acquired interest in 77 mineral claims known as the Lustdust Property, Omineca Mining Division. In 2003, net smelter returns were purchased for these claims. Technical and legal details of this purchase are available in the corporate and legal offices of Alpha Gold. Also during 2003, an additional 8 two-post claims overlying the historic Takla Bralorne Mercury Mine were acquired by purchase. In June 2005 all these claim holdings were converted to eleven "cell" claims


In 2006, six additional "cell" claims were acquired bringing the total to seventeen contiguous claims covering a area of 8,560.75 hectares. A complete list of mineral claims and their expiry dates, pending acceptance of this report, is provided in Table 1. "Cell" claims are geographic blocks with boundaries defined by a computer mapping system. No fractions or ownership disputes are possible with this type of claim.

To the author's knowledge, the property is not subject to any environmental liabilities or other encumbrances that are Alpha Gold's responsibility other than drill-site and access trail reclamation as covered under Permit MX-13-19. The Takla-Bralorne Mercury Mine is being investigated by the Crown Contaminated Sites Branch of the Ministry of Agriculture and Lands but Alpha Gold is not responsible for reclamation or remediation of this historic site.

TABLE 1 LUSTDUST CLAIMS, April 2006				
Claim Name	Tenure No.	Area (ha)	Type of Claim	Expiry Date
Alpha 1	505166	347.159	Mineral	2017.01.28
	514104	603.621	Mineral	2017.01.28
	514105	493.880	Mineral	2017.01.28
	514106	365.990	Mineral	2017.01.28
	514109	694.665	Mineral	2017.01.28
	514111	1205.807	Mineral	2017.01.28
	514114	695.240	Mineral	2017.01.28
	514115	548.900	Mineral	2017.01.28
	514117	274.284	Mineral	2017.01.28
	514119	457.193	Mineral	2017.01.28
	514120	712.906	Mineral	2017.01.28
ALPHA 2	533018	219.652	Mineral	2017.01.28
LUSTDUST	545320	439.372	Mineral	2017.01.28
LUSTDUST	545321	439.653	Mineral	2017.01.28
NAT 1	545682	457.805	Mineral	2017.01.28
NAT 2	545684	439.704	Mineral	2017.01.28
NAT 3	545688	164.923	Mineral	2017.01.28
17 claims		8560.75 ha		



SCALE 1 : 8,500,000




5. ACCESSIBILITY, CLIMATE, LOCAL RESOURCES, INFRASTRUCTURE AND PHYSIOGRAPHY

The property is located approximately 210 kilometers northwest of Prince George, B.C. and 36 km east of Takla Landing, where there is a B.C. rail-line. Lustdust is located immediately west of the old Bralorne Takla Mercury Mine (Minfile 093N 008) and encompasses the Takla Silver Mine (Minfile 093N 009), (Figure 1).


The terrain is moderate, ranging in elevation from 1000-1525 m on the property. Lower elevations are covered by widely-spaced lodgepole pine. At elevations above 1200 m, forest cover consists of overmature spruce and balsam with an undergrowth of white rhododendron. Summers are short and rainy but even under these conditions many of the drainages are seasonal in nature with progressively diminished flows during the late summer and fall. Snow accumulations, during average winters, persist from late September through May-June at the higher elevations. Most of the exploration programs conducted on the property to date have been completed during the June to October field season.

6. HISTORY

The Lustdust property has been explored by a number of operators since the original discovery of the Number 1 Zone in 1944. A synopsis of the exploration history is listed in Table 2. Despite the fact that exposure is limited and that previous efforts have been hampered by poor understanding of the deposit type, new occurrences have been found on a regular basis both along strike to the north-northwest and south-southeast, and at depth.



SCALE 1 : 75,000



KILOMETERS

Figure 2
Lustdust Claim Map



TABLE 2				
EXPLORATION HISTORY SYNOPSIS				
Year	Operator	Claims	Zone	Work Performed
1944		Wow #1	1	Zone 1 discovered and staked
1945	McKee Gp.	Wow #1	1	trenching, 106.7 m of drilling
	Leta Expl. Ltd.			
1952-	Bralorne	Wow 1, MV1	1,2,3	5306 m of trenching,
1954	Mines Ltd.	MV2, M	4b	1429 m of drilling
1960	Noranda Canex		"	7 rock cuts, 34 test pits, 200m hand; and 1508m cat trenching
1963	Bralorne	Wow #1	1	sampling
1964	Takla Silver Mines Ltd.	Wow #1	1	229 m of drifting
1966	Takla Silver Mines Ltd.	Wow #1	1	229 m of underground ddh
1968	Takla Silver Mines Ltd.	Wow #1	1	1337 m of surface and 573 m of
	Anchor Mines Ltd.			underground ddh, 90 kg bulk sample
1978	Granby Mining Corp	MV1, MV2, K,L,M	1, 2, 3, 4b,	Pulse EM, surface ddh
1980	Granby Mining Corp	L,M	1, 2, 3, 4b	airborne mag, VLF, ground mag, VLF; soil survey, 2 ddhs
1981	Noranda Expln. Co	L,M	4b	8 ddhs (7 wildcat); soil sampling; mapping
1986	Welcome North Mines Ltd.	Wow 1, MV, L, M	1, 3, 4B	sampling
1986	Pioneer Metals	Wow 1, MV1, M	1,2, 3, 4b	geological survey
1991	Alpha Gold Corp.	MV1	3	906.6m of drilling in 10 holes
1992	Alpha Gold Corp.	L, M	4b	trenching, 1520m of drilling in 30 holes
1993	Alpha Gold Corp.	L, M	4b	24 ddhs
1996	Alpha Gold Corp.		2,3,4b,4	geology, soils, trenching
1997	Alpha Gold Corp.		2,3,4b,4	soil sampling, 3062.8 m drilling in 16 holes
1998	Alpha Gold Corp.		1, 2, 3	1,103m of drilling in 14 ddhs
1999	Alpha Gold Corp.		3, 4b	3050m drilling in 18 holes, trenching CCS
2000	Alpha Gold Corp.		CCS	4680m drilling in 29 holes.
2001	Alpha Gold Corp.		CCS, Mo	Porphyry Mo-Cu 2945 m in 10 holes; CCS 2664 m in 8 holes
2002	Alpha Gold Corp.	L,M	CCS	7790.4 m in 19 NQ boreholes.
2003	Alpha Gold Corp.	C.G's, L, M	CCS,1,3	7,908 m in 42 NQ boreholes; 37 km soil geochemistry
2004	Alpha Gold Corp.	L,M	CCS,3	6010 m in 21 NQ holes; 724 B horizon soils
2005	Alpha Gold Corp.		East Zone, CCS	5153 m in 16 NQ holes; 587 B horizon soils
2006	Alpha Gold Corp.	514104, 514105, 514117	CCS, GD, Valley	3054m RC drilling in 24 holes; 6855.1m NQ diamond drilling in 32 holes; trenching GD zone


7. GEOLOGICAL SETTING

7.1 Regional Geology

The Lustdust property is located within the Cache Creek Terrane directly west of the Pinchi Fault (Figure 3). The Pinchi Fault can be traced for 600 km through north-central B.C. and is believed to have been a major thrust fault which was later reactivated as a large right-lateral strike-slip fault (Paterson, 1977). In the project area, the Pinchi Fault separates Cache Creek rocks from the Jurassic Hagem Batholith and Triassic-Jurassic Takla rocks to the west. The Cache Creek Group is of Pennsylvanian-Permian age and consists of a >500 kilometer-long, >3000 meter thick, complexly deformed sequence of interbedded argillites, cherts, carbonates, and mafic to ultramafic volcanic and plutonic igneous rocks. Alpine peridotites and ophiolite fragments are locally present, especially to the north of the Lustdust property (Soregaroli, 1999, Schiarizza and MacIntyre, 1999).

Although some rock units are locally metamorphosed to blueschist facies, the overall metamorphic grade throughout the area is low. The argillites and cherts are typical, fine-grained, thinly bedded deep-marine sediments (Monger, 1977). The volcanic rocks are tholeiitic and include andesitic to basaltic tuffs, flow-breccias, and pillow basalts - all of oceanic affinity. The carbonates are dominated by bioclastic to micritic and algal-bound shallow-water facies limestones, interpreted to have been deposited in a carbonate bank or reef environment (Monger, et al, 1991). Regional studies have emphasized the observation that contacts between most of the different lithologies are abrupt and probably are faults. However, detailed studies, executed close to Lustdust (Sano and Struick, 1997), have found limestone conglomerate and sandstones with volcanic fragments, and limestone fragments within the argillite-chert section. Similar relationships are seen in core at Lustdust and locally show uninterrupted gradation from massive limestones to mafic volcanic dominated successions.

The entire package is folded with a well-developed axial planar foliation with a north-northwest strike trend typical of the entire Intermontane Belt in which the Cache Creek Terrane lies (Gabrielse and Yorath, 1992). A wide range of Jurassic to Tertiary intrusions cuts the Cache Creek Assemblage and many of these are emplaced along the prominent NW-trending structures and stratigraphic breaks. Numerous mercury occurrences are present along the length of the Pinchi Fault (Albino, 1987) and a few gold and base metal occurrences are present within Cache Creek rocks near the Pinchi fault including the Lustdust, Indata and Axelgold properties. There are at least two alkalic gold-copper Porphyry systems in the immediate Lustdust area: J49 and Axel Properties (Schiarizza, 2000).



Legend












- | | | | |
|---|---|---|---|
|  | Early Cretaceous Mitchell & MacDonald-Embryo L. batholiths |  | Lustdust porphyry-skarn-manto vein system |
|  | Early Cretaceous Germansen Batholith |  | Alkalic Porphyry occurrences |
|  | Late Triassic to Early Cretaceous composite Hogem Batholith |  | Pinchi Fault (Cache Creek - Quesnel terrane boundary) |
|  | Middle Jurassic Spike Peak intrusive suite |  | Stikine - Cache Creek terrane boundary |
|  | Late Permian to Early Triassic Sitlika Assemblage diorite |  | Road |
|  | Undifferentiated supracrustal rocks | | |

Figure 3 - Regional Geology (Ray, G.E. et al, 2002)

7.2 Lustdust Property Geology: Summary

The Lustdust property is underlain entirely by Permian Cache Creek units that form upright to overturned asymmetrical, west-dipping, north-plunging folds. These folds parallel the north-northwest trending Pinchi fault that lies along the eastern property boundary. The stratigraphy strikes N-NW with generally vertical to moderate westerly dips. Very little bedding is preserved and structural information is rare except in road cuts. The explored part of the property is dominated by a variety of intrusions which cut carbonate rocks interbedded with graphitic and calcareous phyllites, cherts, cherty argillites, and mafic tuffs (Figure 4).

A composite intrusive center and linear dyke array, the "Glover Stock", occurs in the center portion of the property. The stock is well-zoned and includes rocks ranging from mafic to felsic in composition. Pervasiveness of biotite hornfels and skarn increases towards the stock (Evans, 1998). Some of the intrusive phases contain significant amounts of magnetite and appear to be responsible for the large magnetic anomaly shown on published regional maps and in Alpha's 2000 ground-magnetics survey (Butler and Jarvis, 2000). Geochemical analyses, of several different intrusive phases, indicate that some have borderline alkalic composition similar to intrusions related to Au-Cu porphyry deposits elsewhere in the region, including the "Babine Intrusions". Others have calc-alkaline compositions typical of B.C. copper skarns (Ray and Webster, 1997).

Several styles of mineralization that are zonally related to each other are present on the property. From most proximal to most distal from the Glover Stock, they are:

1. **Molybdenum-Copper-Gold Porphyry** consisting of quartz-K-spar, pyrite, molybdenite and/or chalcopyrite veinlets associated with potassic, sericitic, and propylitic alteration in intrusive rocks (Glover Stock).
2. **Multi-stage Garnet-Diopside skarn** cut by Cu-Au-Ag-Zn bearing structures with surrounding dispersed Cu-Au mineralization (Canyon Creek Skarn).
3. Structurally and stratigraphically controlled **massive sulfide Zn, Au, Pb, Ag, Cu replacement bodies** [CRD] (4b, 3, and 2 Zones) and their oxidized equivalents.
4. **Sulfosalt-rich veins** (Zone 1) which follow faults and are strongly associated with fine-grained, linear, felsic dykes containing high values of Au, Ag, Pb, Zn, Sb and Mn.
5. **Mercury** mineralization in limestone proximal to the Pinchi Fault.
6. **Sediment-hosted gold** mineralization in limestone.




Figure 4 - Lustdust Property Geology (Ray, G.E. et al, 2002)

7.3 Supracrustal Rocks

Interpretations of primary stratigraphy are challenged by the strong regional deformation. In the area of extensive drilling of the 4b and Canyon Creek Skarn zones, several coherent rock panels may be described as follows:

1. Hanging-wall assemblages to the Canyon Creek Skarn are dominated by a sequence of thinly compositionally laminated, siliceous and/or argillaceous phyllites often with strong biotite compositional layers. These rocks are interpreted as ribbon cherts by British Columbia Geological Survey geologists with extensive regional experience. The argillaceous, clastic component, of these rocks may increase towards the skarn – calc silicate horizon, particularly to the south towards the 4b zone.
2. Skarn assemblages are developed in weakly compositionally-layered limestones, in calcareous mafic tuffs, or rarely in siliceous phyllites.
3. Footwall assemblages to the Canyon Creek Skarn are dominated by rocks which are typically described as cherty argillites and/or cherts. Rocks in the footwall are similar to hangingwall rocks but qualitatively appear to have a higher proportion of quartz compositional layers and decreased biotite lamella.

Stratigraphic units are more fully described below:

Limestone (LS)	Light to medium grey, sucrosic, recrystallized limestone, locally with weak stylonitic cleavages. These rocks bleach to off-white adjacent to skarn fronts. They may contain numerous internal horizons of both dark grey clastic beds and mafic tuffaceous horizons.
Calcareous Phyllite (CP)	Dark grey-brown, argillaceous interbeds are intercalated with thin, centimetre scale, calcareous lamella
Calcite Knot Limestone (Lcs)	Calcite knot limestones may contain either white cm scale calcite aggregates within a darker grey matrix, or they may be a gradational unit to mafic tuffs where 10-30% oval to cusped calcite clasts are supported by a strongly calcareous, light to medium green matrix.

Siliceous Phyllite (SP)	These rocks are defined by compositional layers formed by alternating foliation parallel biotite +/- lesser white micas, with quartz compositional layers. The protolith of these rocks is interpreted, by many workers, as ribbon cherts.
Chert (C)	With an increase in quartz content, to greater than 75% rock volume, the rocks are logged as cherts. Minor increases in biotite compositional layers may shift these rocks into a phyllitic chert (PC) field.
Argillite (A)	Argillite is a composite unit that includes a wide range of fine-grained, essentially non-calcareous, carbonaceous, thinly bedded sedimentary rocks. It includes argillites (A), cherty argillites (CA), thinly bedded cherts, carbonaceous argillites (CA). Graphitic layers are common throughout. Locally, the thinly bedded units contain fine-grained, continuous pyrite or pyrrhotite layers that appear to be part of the original sediments. As with all supracrustal rocks, these units are strongly deformed.
Mafic Tuffs (MT)	Mafic tuffs are well-foliated and often well compositionally layered dark green, to green and white mottled rocks with highly chloritic and locally calcitic matrices. The chlorite is interpreted to result from alteration of mafic-intermediate tuffaceous materials. 1-30 cm limestone fragments are the dominant clasts, but fragments of intermediate and mafic volcanic rocks are also present. These rocks contain up to 2% finely disseminated pyrite and/or pyrrhotite and are geochemically anomalous for Pb, Zn, and Cu. Grading in limestone fragment size is common. Evans (1997, 1998) believed that there was only one mafic tuff unit and that it was a good marker bed. Previous fieldwork and core logging show that there are multiple mafic tuff units in the section and they show enough lateral variation that their utility as marker beds may be limited.

7.4 Intrusive Rocks

Mineralization throughout the Lustdust property shows a close association with the Glover Porphyry - a composite intrusive complex consisting of stocks and dikes ranging from diorite to monzonite to rhyodacite. Cu-Au skarn forms abundantly along stock and dike contacts (and replaces these rocks) and Zn-Au-Pb-Ag-Cu replacement mineralization is locally well developed along dike margins at more distal locales. Overall, mineralization shows zonation relative to the inferred center of the Glover Porphyry complex. Some of the compositional variations can be attributed to potassic alteration and silicification, which change the original intrusive composition and appearance in hand specimen, but the majority of the phase differences are real. Intrusive rock units include:

Monzonite (M)	A medium-grained equigranular to weakly porphyritic rock composed of plagioclase>K-feldspar, abundant elongate hornblende and euhedral biotite. Quartz is present, but in minor amounts. This unit crops out extensively as dikes throughout the southern and southwestern area, and the dikes seem to widen towards the 4b Zone. These dikes locally host replacement mineralization along their flanks.
Megacrystic Monzonite (Mp)	This intrusive phase is defined by the presence of very strongly plagioclase +/- quartz porphyritic monzonites. Contacts of these rocks with finer grained phases may be gradational.
Quartz Monzonite (QM)	These rocks contain 10 -15% free quartz as discrete, millimetre scale phenocrysts. The rock is also hornblende and biotite porphyritic and may be beginning to shift into a granodiorite field.
Diorite (D)	Diorites are fine to medium-grained, medium to dark gray-green and composed of plagioclase, biotite and hornblende phenocrysts. Accessory magnetite is locally abundant. The phases are distinguished largely on the presence and the abundance of biotite and hornblende. This distinction can be difficult to make in the finer-grained units where potassic alteration has replaced the hornblendes with secondary biotite. Color is determined by mafic phenocryst content and the degree of chloritic alteration.
Monzodiorite (MD)	A shift to increased percentages of fine-grained matrix plagioclase and a decrease in mafic phases, hornblende and biotite are the characteristics of this unit. Free quartz is not identified.
Felsic Dykes (Fd)	Felsic dykes occur across the property. These are weakly porphyritic felsic rocks with sparse to prominent 1-3 mm quartz and feldspar phenocrysts set in a sugary fine-grained matrix of quartz and feldspar. They are locally well flow-banded with banding generally parallel to their overall orientation. Felsic dykes are often pervasively argillically altered or silicified making them difficult to distinguish from altered fine-grained monzonite. Felsic dykes in the Number 1 Zone commonly have vein mineralization along one or both contacts.
Felsic Dykes (Fpd) Plagioclase Porphyritic	Distinctive elongate, sericitized feldspar phenocrysts are abundant within this rock matrix and may exceed 35% rock volume. The rock also contains 5-8% coarse quartz phenocrysts.

Mafic Dykes (Bd)	Medium to fine-grained, undifferentiated mafic dykes.
Ultramafics (UM)	Green to dark black, uralitically altered, ultramafic intrusions. In their unaltered state, the intrusions are likely pyroxenites. Elevated interstitial magnetite is common. Pyrrhotite is locally noted. The intrusions likely trace major strands of the Pinchi Fault. True brittle-ductile fabrics are common within these intrusions.

7.5 Structure:

Rocks underlying the Lustdust property have experienced multiple deformational events. In the absence of geochronological data, definitive age relations between these events are difficult to establish. However, overall map patterns, rock fabrics and discordant rock fabrics in drill core suggest that at least two penetrative deformational processes, D1 and D2, have influenced the current map pattern.

The development of a pronounced planar S1 fabric, often co-planar to bedding and primary compositional layers, defines an early D1, deformational process. These fabrics are most likely axial planar to the tight to isoclinal, upright to west overturned, east-verging folds. The data of Ray et al., (2002) suggest these folds plunge approximately 40-50° to the north-northwest. The distribution of bedrock lithology has been profoundly influenced by this event.

The rotation of S1 fabrics is evidence for post D1 processes. Although S1 fabrics are clearly rotated, S2 penetrative foliations are weakly developed and may be measured in only very selective core and rock samples. Ray et al. (2002) suggest that D2 folds have similar orientations to D1 folds, but tend to be slightly more open, and have shallower, 20° northwest plunges.

Regionally, folds in the Cache Creek assemblage are typically open (Schiarizza and McIntyre, 1999), but on the Lustdust property folds are generally asymmetrical and overturned with short, shallow, west-dipping western limbs and long, steep, west-dipping eastern limbs. Locally they are isoclinal. Tight folding is likely due to buttressing against the Pinchi Fault, which is believed to have originally been a major thrust fault (Paterson, 1977). Where observed, these folds have a 10-60 degree N-NW plunge and minor axial plane shears are common. The noses of antiforms are structurally thickened and fractured zones favorable for manto mineralization (Evans, 1998; Megaw, 1999).

The entire property has a strong NW-trending, grain reflecting bedding, tight asymmetric folding, and bedding plane faults. This structural fabric closely controls intrusive emplacement and most of the dykes of the Glover stock are strongly elongated along this N-NW structural grain. The most important, and consistent, fault structures demonstrated in drill core are roughly coplanar to bedding. Some of these faults have the appearance of early east verging reverse faults, which are largely lithologically controlled and mostly identified in the immediate hangingwall to the Canyon Creek Skarn. These faults may be rotated into slightly steeper positions by latter extension faults.

The strongest and most strike discordant structural zone on the property is the structural zone and dyke system which hosts the Number 1 veins. This mineralized fault structure has a nearly north-south strike and moderate to steep west dip. In marked contrast, all structures, including lithology and major skarn bodies on the Lustdust property have strike relationships which average 150° to 160° and steep westerly dips.

Compilation of the sub-surface data with the surface geological plans suggests that right stepping lithologic offsets, which occur both to the north and south of Canyon Creek, are related to fold vergence effects - an east verging, right stepping antiform - rather than a fault related offset.

Mapping of carbonates on a property-wide scale (Evans 1997; 1998) shows a wide outcrop band in the southern portion of the property that appears to decrease in width to the north, largely disappearing at Canyon Creek. This may be an artifact of limited outcrop exposures as integration of the subsurface information from drilling suggests the northern continuity of the most easterly limestone package may be significantly better than initially interpreted (Figure 4). The limestone is asymmetrically folded and plunges north at 15-20°.

8. DEPOSIT TYPES

Carbonate replacement deposits (CRD) typically grade from lenticular or podiform bodies developed along stock, dike, or sill contacts to elongate-tabular bodies referred to as chimneys and/or mantos depending on their orientation. Limestone, dolomite and dolomitized limestones are the major host rocks. Ores grade outward from sulfide-rich skarns associated with unmineralized or porphyry-type intrusive bodies to essentially 100% polymetallic massive sulfide bodies. Both sulfide and skarn contacts with carbonate host rocks are razor sharp, and evidence for replacement greatly outweighs evidence for open-space filling or syngenetic deposition (Titley & Megaw, 1985). In reduced, high to low-temperature systems, proximal to distal metal zoning generally follows: Cu (Au, W, Mo), Cu-Zn (Ag), Zn-Pb-Ag, Pb-Ag, Mn-Ag, Mn, and Hg. This zoning may be very subtle and large scale (Prescott, 1916; Morris, 1968) or tightly telescoped and smaller scale (Graf, 1997).

Many different features of CRDs tend to be well-zoned at district, deposit and hand-sample scales. The most important zonations are: 1) Ore and gangue mineralogy and metal contents; 2) Orebody geometry; 3) Intrusive geometry and composition; 4) Structural controls on mineralization; 5) Alteration; and 6) Isotopic characteristics of wallrocks. In general, the largest systems show the best-developed zoning and repetition of zoning and paragenesis. Zoning tends to be most extensive in the elongate manto and chimney systems where individual zones may extend over kilometers vertically and laterally (1998). Zoning in large contact skarn systems is typically more compressed because of telescoping and repeated overprinting (Graf, 1997). In all cases, multi-phase mineralization is a reliable indicator of large systems.

CRD mineralization is associated with polyphase intrusions that evolve from early intermediate phases towards late, highly evolved felsic intrusions and related extrusive phases. The intrusions most closely related to mineralization are usually the most evolved phases and these are not exposed in many districts. Dikes and sills characterize the intermediate reaches of CRDs and there is often evidence for multiple dike/sill

emplacement events. These intrusions may be compositionally homogeneous or there may be compositional evolution between dike/sill phases (Graf, 1997). Textures range from porphyritic to aphanitic, locally with narrow gradations between textural domains. Chimney and replacement veins are the most common orebody types associated with these intrusions, although mantos locally occur along sill contacts. Intrusive stocks commonly occur beneath or adjacent to the most proximal portions of CRD systems, although in many cases they do not crop out. Where intrusions are exposed, they are generally less than 5 km² in areal extent. These stocks are generally polyphase with compositions grading from early diorite to late granite. Texturally, these intrusions range from equigranular to porphyritic and from massive to highly fractured. The central stocks may be barren, contain porphyry copper or molybdenum systems, or have marginal zones with porphyry copper or molybdenum affinities (Megaw, 1998). In many systems, the early phases of the intrusion have associated skarnoid or barren skarn, whereas skarn and ore mineralization are related to later, more highly differentiated phases (Meinert, 1995 and 1999; Graf, 1997; Megaw et al., 1998).

Structural fabrics are the dominant control on mineralization in CRDs, as they control intrusion emplacement and channel ore fluids into favorable host strata. Most CRDs lie in fold-thrust belts on major structural domes, arches, anticlines, synclines or homoclines, and most districts have structural grains controlled by faulting and fracturing related to regional deformation (Megaw et al. 1988). Orebodies are often elongate with parallel, district-wide structural trends, but may not be restricted to a given structure over great lengths.

The gradations seen in single orebodies or districts suggest that the various manifestations of the deposit type can be considered part of a spectrum (Einaudi et al. 1982; Megaw et al. 1988; Titley, 1993) ranging from:

1. Stock contact skarns: formed against either barren or productive stocks
2. Dike and sill contact skarns
3. Dike and sill contact massive sulfide deposits
4. Massive sulfide chimneys
5. Massive sulfide mantos
6. Epithermal veins
7. "Carlin" style sediment hosted deposits

Several features make CRDs highly desirable mining targets including: **1) Size-**CRDs average 10-13 million tons of ore and the largest range up to >50 million tons; **2) Grade-**ores are typically polymetallic with metal contents ranging from 2-12% Pb, 2-18% Zn, 60-600 g/T Ag, Tr-2% Cu and Tr-6 g/T Au. Many have by-product credits for Cd, W, In, Ga, Ge, Bi, and S; **3) Deposit morphology-**orebodies show good continuity; **4) Extraction and Beneficiation-** CRDs are typically metallurgically docile, amenable to low-cost mining methods, and the environmental footprint is minimal.

Massive sulfide bodies lacking an associated intrusion characterize the distal zones of CRDs. These commonly have the form of high angle to vertical slab-like replacement veins; elongate pipe-like chimneys; or low angle to horizontal tabular or elongate, tongue-shaped, crudely stratabound mantos. Mantos may be developed entirely within selected beds or groups of carbonate beds, or may occur with one or more non-reactive, relatively impermeable sedimentary or intrusive rock contacts.

Development of carbonate rock alteration in CRDs, like mineralization, is highly variable in type and in scale. The major alteration types are:

1. Skarnoid or hornfels:

These are typically very fine-grained, mineralogically simple, calc-silicate and silicate assemblages formed through thermal metamorphism without significant addition of outside components. Skarnoid typically forms from a limestone or shaly limestone precursor, whereas hornfels forms from shale or limy shale precursors. Hornfels and skarnoid commonly develop in the thermal aureole around the largest volume (often early) intrusive phase and may aid in ground preparation for later metasomatic events. Hornfels mineralogy may be zoned with respect to the thermal center, commonly with pyroxenes proximal and biotite more distal. Skarnoid and hornfels often contain abundant fine-grained pyrite or pyrrhotite, but seldom significant amounts of ore-metal sulfides unless it has been overprinted by subsequent hydrothermal events.

2. Skarn:

Skarns are fine to very coarse-grained, often mineralogically complex, calc-silicate or calcic-iron silicate assemblages formed through metasomatism with significant addition of outside components. **Endoskarn** is skarn formed at the expense of intrusive rock, **exoskarn** is skarn formed at the expense of wallrocks to the intrusion, most commonly carbonates. Skarn commonly develops around lesser volume, more fluid-rich intrusive phases and may overprint hornfels or skarnoid to varying degrees. Anhydrous calc-silicate minerals (dominantly pyroxenes and garnets) characterize the early "**prograde**" skarn phase generated during rising temperatures related to magma emplacement. Hydrus calc-silicate minerals (dominantly amphiboles, chlorites, and clays) formed at the expense of predecessor prograde minerals characterize the later "**retrograde**" skarn assemblage. Retrograding occurs as temperatures drop and variable amounts of magmatic fluids and groundwater invade the skarn zone. Sulfides may be co-deposited with the calc-silicates, but more commonly are introduced along structures that cut the skarn, replacing skarn minerals and unskarned wallrocks. Complex mineralized skarn systems typically show multiple intrusive phases and a repetition of sulfides replacing calc-silicates, presumably reflecting successive intrusive and hydrothermal events. In some systems, different compositions of skarn and sulfides characterize each phase (Megaw et al., 1998).

3. Marbleization and recrystallization:

These are present in virtually all CRD systems and range from narrow zones around mineralization to zones 100s of meters wide (Tittley & Megaw 1985; Megaw et al. 1988).

4. Silicification or Jasperoid development:

Fine-grained silica replacements of carbonate rocks, with or without appreciable amounts of metals, and are very common in the peripheries of some CRD systems (Tittley & Megaw 1985; Megaw et al. 1988).

9. MINERALIZATION:

9.1 General

The Lustdust porphyry-skarn-replacement system is at least 3000 m long and 1000 m wide (Figure 4). The property is systematically zoned from a Mo-Cu-Au Porphyry system to Cu-skarn to Zn-replacement mantos to Ag-Pb-Zn replacement veins developed along an echelon mineralized zones extending away from the porphyry. The entire Lustdust system, outboard of the porphyry, is auriferous (0.5 to >1 g/T Au values are common) and associated with a minimum of three mineralized skarn horizons.

The Canyon Creek Skarn is now known to be zoned over at least 500 m vertically and increasingly shows the polyphase intrusive and mineralization characteristics typical of Cu-Zn skarn-replacement systems throughout the American Cordillera, such as San Martin, Zacatecas, Mexico and Antamina, Peru. So far, despite widespread anomalous values, no significant volumes of porphyry-style mineralization with economic grades have been found.

Principle characteristics of the main mineralized zones may be summarized as follows:

9.2 Zn-Pb-As-Sb Vein Zone: Number 1 Zone

The Number 1 Zone, located at the southern end of the property, was the site of the 1944 discovery of mineralization on the property. Here, the limestone and graphitic phyllites are cut by numerous monzonite and felsic dikes. Sulfosalt veins composed of nearly massive pyrite, sphalerite, galena, jamesonite, stibnite, arsenopyrite and freibergite with lesser open-space filling quartz and calcite occur both within the sedimentary rocks and along dike contacts. Dunne and Ray (2002) also report traces of very fine-grained calc-silicates in these bodies. Three separate veins have been recognized, all of which appear to dip steeply west. Felsic dikes are closely related to all three veins, but the veins do extend beyond the dikes in many places. The Number 1 Zone has the strongest structural control of any occurrence on this property. The presence of a regional antiformal crest is likely to be important to the development of significant mineralized zones as is the main fault structure.

Argentiferous Manganese Oxide Mineralization (AMOM) occurs throughout the Number 1-Zone. AMOM is a typical distal alteration product in certain major CRD systems (Megaw, 1998) and the Number 1 Zone is strongly anomalous in Mn (Evans, 1997). Based on inclusion chemistry and mineralogic relationships, Dunn and Ray (2002) suggested that the mineralization in this zone might be related to high sulphidation-type veins. However, the alteration mineralogy and textures of quartz and other gangue minerals do not support the high sulphidation model for these veins.

The principal vein was explored by underground drifting and drilling in the 1945 and 1964-65 seasons. The three ore-shoots (minimum 2 m true widths) above the adit level were reported to grade 3.6 g/t Au, 780 g/t Ag, and 5% combined Pb and Zn with 5% Sb. Historic drilling had notoriously bad recovery problems, so in many cases grade was not reported for potentially significant intersections.

Compilation of all available data during the 2003 exploration season clearly indicated that the currently known strike length of the Number 1 Fault exceeds 750 m with a significant mineralized zone developed over approximately 450 m.

9.3 Zn-Au-Ag-Pb CRD Mineralization: Number 2, 3, 3 Extension, 4b and East Zones

Mineralization in these zones consists of roughly stratigraphically concordant massive sulfide bodies ("mantos") and their oxidized equivalents. The mantos are best developed along permeable and karsted (?) carbonate beds in close proximity to chlorite-altered mafic tuff beds. The mantos occur through the Number 2 to Number 4b Zones and appear to merge into the Canyon Creek Skarn Zone. Drilling results have failed to find substantial discordant chimney feeders to these mantos, although narrow feeders may have been hit locally (Megaw, 1999). The mantos occur dominantly in structurally thickened and deformed zones along the crests of antiforms. There is some evidence for nesting, or repetition, of mantos in successive limestone beds, giving an overall morphology reminiscent of the stacked "saddle-reef" mantos.

Number 2 Zone

The Number 2 Zone is a minor oxidized replacement zone similar to the Number 3 Zone. The Number 2 Zone is located very close to the crest of a regional antiform which lies just north of the Number 2 Zone trenches. Surface sampling indicates an average of 2.3 g/t Au, 109 g/t Ag, 2.16 % Zn and 2.09 % Pb across an average of 5.3 meters true width. This zone has a strike length, based on surface oxidation, of approximately 200 meters. Its continuity at depth is much more problematic as significant intersections have not been obtained from drill holes to date.

Number 3 Zone

The Number 3 Zone contains the largest identified CRD resource identified to date at Lustdust. It is thoroughly oxidized to depths of greater than 100 meters from the surface. The style of mineralization may be highly amenable to low cost heap-leach extraction processes.

The thickest portions of this manto zone occur in carbonates surrounding a mafic tuff bed along the crest of a regional-scale antiform. The manto may have the form of an oxidized saddle reef replacement body. Drilling has failed to find a feeder vertically beneath it, suggesting that it was probably fed from one end with fluid migration concentrated along the non-reactive tuff bed. Evans (1997) felt that the conduit for this system was down dip along the west limb of the antiform (possibly with a NW rake). This zone, based on the trace of oxidation exposed in surface trenches, has a strike length exceeding 600 meters. The Number 3 zone appears to weaken to the south, south of the Number 2 Zone trenches. The northern extension of the Number 3 Zone has received very limited exploration, as has the down dip extensions to this mineralization.

Number 4b Zone

The Number 4b Zone CRD manto is developed along the 4b Antiform, a tight fold, with 60-degree west dips and a 10-15 degree plunge to the NW. The trace of this fold lies some 300 meters to the west of the Number 3 Zone antiform. The two zones are linked by a north-northwest plunging synform. Mineralization occurs as a series of aligned, discontinuous (?) massive sulfide pods (with sparse calc-silicate minerals) following the crest of the fold and also along the contact between limestone on the east and hornfelsed graphitic phyllites to the west. A mafic tuff horizon within the limestone appears to be a major conduit for fluid movement, as is seen in the Number 3 Zone. The 4b Zone is, however, essentially unoxidized: sphalerite, arsenopyrite, coarse-grained well-zoned pyrrhotite, and pyrite are prominently displayed in surface trenches along the zone.

East Zone

The East Zone was discovered in 2005 by drilling a coincident gold-arsenic soil geochemistry anomaly approximately 300 metres east of the Canyon Creek Skarn. This gold-silver-copper-zinc massive sulfide zone is completely "blind" and has been intersected by five drill-holes over a strike length of 150 metres. It is open along strike to the north and in both dip directions. The massive sulfide mineralization consists of pyrite, sphalerite, arsenopyrite, and chalcopyrite. The preliminary interpretation is that the zone is a carbonate replacement similar to the Number 3 and Number 4B zones.

9.4 Canyon Creek Skarn (Number 4 Zone)

The Canyon Creek Skarn [CCS] or the Number 4 Zone, is the skarn-replacement zone lying north of the 4b Zone. The discovery of this skarn is recent enough that it was not included in Ray and Dawson's (1998) compilation on B.C. skarns. Prior to the 2001 season, this zone had been cut by 41 drill holes (97-9, 10, and 11; LD99-03 through 12; and LD00-02 through 29) and a few trenches (Evans, 1997, 1998; Megaw 1999, 2000). A high percentage of the pre-2001 holes in skarn intercept high-grade Cu-Au mineralization along structures cutting garnet-pyroxene skarn. Some of these mineralized structures were surrounded by zones of dispersed mineralization a few meters wide (Megaw, 1999; 2000).

At shallow levels, the skarn is composed of early coarse-grained green-tan grossular-andradite garnet with minor fine-grained greenish-yellow diopside and rare vesuvianite or pyroxene (Ray et al., 2002). Specularite is locally very common as euhedral plates. At depth, a brown garnet stage crosscuts and overprints the green stage, and at even greater depths, a red-brown garnet stage appears (Megaw, 1999). These minerals replace massive limestone and locally replace intrusives (endoskarn). Drilling in 2001 showed that endoskarn increases with depth (cf. LD01-44, 45). Biotite hornfelsed siliceous phyllite is also overprinted by skarn, especially on the north side of Canyon Creek. Mafic tuff units are altered to distinctive green, banded chlorite-garnet units with 5-15% disseminated pyrite and trace chalcopyrite and sphalerite.

Retrograde hydration of the garnet-diopside skarn also increases with depth. In the retrograde zones, the brown-red, brown and green garnet stages are hydrated to a cream-colored mass of very fine-grained amphibole, chlorite, quartz, and clays or dark grayish-green masses of felted chlorite, locally preserving the shapes of dodecahedral garnet crystals. Retrograde alteration is often accompanied by a dramatic increase in magnetite, both as fine-grained masses and as pseudomorphs after bladed specularite, and increased amounts of chalcopyrite (Megaw, 2000, Ray et al., 2002)

Mineralization in the skarn occurs as Ag and Au-bearing chalcopyrite and bornite with abundant pyrite, variable sphalerite, and rare arsenopyrite and stibnite emplaced along and surrounding structures that cut the skarn (Megaw, 1999). Much of the sulfide replaces skarn silicates. Numerous stages of sulfide mineralization are identified as:

1. Chalcopyrite deposited in interstices and along garnet grain boundaries.
2. Early pyrrhotite (often later pseudomorphed to pyrite) with minor chalcopyrite and locally intergrown with sphalerite.
3. Pyrite or pyrrhotite (pseudomorphed to pyrite) that is brecciated and healed with later sphalerite or replaced by chalcopyrite.
4. Massive to dispersed, banded and chaotic chalcopyrite along structures and replacing adjoining skarn.
5. Magnetite with interstitial chalcopyrite and/or sphalerite, pyrite or pyrrhotite.
6. Sphalerite with chalcopyrite cut by later pyrite veinlets.
7. Massive sphalerite, brecciated and healed by chalcopyrite and sphalerite.
8. Mineralized skarn, brecciated and healed with epithermal style chalcedonic quartz.
9. Calcite veins filled with Au sulfides/sulfosalts cutting skarn.

The skarn silicates tend to end abruptly and massive sphalerite-chalcopyrite-pyrite-pyrrhotite mineralization is locally well-developed along the contact of skarn with recrystallized limestone (marble front). It is near this front that the very high-grade gold grades associated with the 2002 drilling have been recognized (Oliver, 2002). High-grade gold and sulphide-rich replacement bodies may be considered transitional mineralization between the skarn and 4b style of replacement mineralization.

10. 2006 EXPLORATION PROGRAM

The 2006 exploration program was directed toward expanding the known geological resource on the Lustdust property by:

1. Fill-in exploration diamond drilling of the Canyon Creek Skarn (CCS) including the highly favorable footwall zone.
2. Diamond drilling and trenching coincident arsenic-zinc soil geochemistry anomalies over the favorable limestone unit along strike to the north of the Number 3 Manto oxide zone.
3. Refining the geologic base-map of the property.
4. Diamond drilling a gold-arsenic soil geochemistry anomaly west of the Number 4b Zone.
5. Evaluating the sediment-hosted gold potential of a large area centered on the historic Takla-Bralorne Mercury Mine by reverse circulation and follow-up diamond drilling.

The 2006 exploration work on the Lustdust property was completed in accordance with Amended Permit MX-13-19 as issued by the Ministry of Energy and Mines (MEM) on June 5, 2006 and November 22, 2006. The MEM work approval number for the project was 06-1000323-0605. Timber clearing for drill-sites and access trails was covered by Free Use Permit F15044 as issued by the Ministry of Forests.


11. DIAMOND DRILLING PROGRAM

The diamond drilling program utilized a Longyear 38, skid-mounted drill under contract from Britton Bros. Diamond Drilling Ltd. based in Smithers, B.C. Drilling was undertaken using regular wireline equipment.

Access to the drill sites utilized the extensive network of trails existing on the property. New access trails and drill pads were constructed using a Cat 322 excavator under contract with Hat Lake Logging Ltd. of Fort. St. James, B.C.


In total, 6 855.1 meters of NQ core, distributed among 32 holes, were drilled and 1 125 split core samples were taken for analysis during the 2006 Lustdust exploration program. Holes LD06-01 to LD06-30 were drilled during the period between June 12, 2006 and August 15, 2006. Holes LD06-31 and LD06-32 were drilled between November 28, 2006 and December 9, 2006. Collar locations and projected traces for these boreholes are plotted on Figure 5 and Figure 6. Core was logged on site by Daryl J. Hanson, P.Eng. All lithologic, assay, survey and RQD logs are compiled and presented in Appendix I. RQD was the only quantitative geotechnical data collected. The presence of gouge and slickensides are noted on the lithologic logs. Digital photographs of the core are stored in Alpha's database.

Upon completion of each hole, the collar was marked with a labeled pole. Drill-hole collars and new access trails were surveyed by Nex Tech of Fort St. James using a GPS system operating in differential mode. In this mode, precision of the UTM location was



SCALE 1:5,000

Kilometers



Lust Dust Project - 2006 Drilling

24 Apr 07

determined to be less than 3.0 meters. A summary of survey information, including UTM collar co-ordinates, collar elevation, azimuth, dip and total depth is presented in Table 3. Holes LD06-30 , LD06-31, and LD06-32 had not been collared at the time of the survey.

The attitude of the collar was measured using a Brunton compass with a declination of 23° while down-hole surveys were conducted using a Reflex EZ-Shot digital instrument. Down-hole readings for azimuth, inclination, and magnetic field were taken at approximately 60 metre (200 ft.) intervals in all holes except LD06-01, LD06-02, LD06-30, LD06-31 and LD06-32. It should be noted that the Reflex EZ-Shot azimuth readings can be influenced by magnetic minerals.

TABLE 3						
2006 DIAMOND DRILL HOLE SUMMARY DATA						
DDH-ID	UTM E	UTM N	ELEVATION (m)	LENGTH (m)	AZIMUTH	DIP
LD06-01	347490.5	6161454.0	1420.4	218.5	080	-55
LD06-02	347490.5	6161454.0	1420.4	261.2	080	-65
LD06-03	347372.3	6161562.5	1394.4	227.7	084	-55
LD06-04	347549.6	6161559.0	1381.0	157.6	084	-55
LD06-05	346967.9	6161748.4	1373.9	197.2	060	-65
LD06-06	346967.9	6161748.4	1373.9	206.4	060	-75
LD06-07	346993.0	6161725.9	1381.2	163.7	062	-70
LD06-08	346993.0	6161725.9	1381.2	188.1	062	-80
LD06-09	347068.7	6161714.5	1379.6	47.9	064	-45
LD06-10	347027.4	6161692.8	1397.2	90.5	064	-55
LD06-11	347027.4	6161692.8	1397.2	121.0	064	-75
LD06-12	346927.9	6161737.3	1387.5	239.9	060	-65
LD06-13	346927.9	6161737.3	1387.5	306.9	060	-75
LD06-14	346962.3	6161919.9	1342.5	214.9	067	-55
LD06-15	346859.3	6161889.4	1360.9	328.3	064	-60
LD06-16	346771.9	6161868.7	1374.9	511.2	064	-65
LD06-17	346771.9	6161868.7	1374.9	538.6	064	-75
LD06-18	346771.9	6161868.7	1374.9	401.4	064	-55
LD06-19	347362.2	6161666.9	1366.3	108.8	112	-45
LD06-20	347362.2	6161666.9	1366.3	60.0	112	-60
LD06-21	347362.2	6161666.9	1366.3	38.7	122	-45
LD06-22	347389.9	6161655.2	1348.7	75.3	253	-45
LD06-23	347358.6	6161619.0	1375.5	90.5	100	-45
LD06-24	347358.6	6161619.0	1375.5	44.8	100	-60
LD06-25	347358.6	6161619.0	1375.5	81.4	100	-70
LD06-26	346995.5	6161403.8	1494.0	267.3	090	-60
LD06-27	346949.1	6161382.5	1506.6	124.0	088	-45
LD06-28	346946.8	6161431.6	1484.8	152.8	088	-60
LD06-29	346833.8	6162174.9	1371.2	631.5	046	-75
*LD06-30	349264.3	6161330.2	1101.0	191.1	000	-90
*LD06-31	349552.9	6159743.1	1054.9	303.9	000	-90
*LD06-32	349485.0	6159755.0	1055.0	264.2	087	-51
32 holes				6,855.1 m		

* hole not surveyed

11.1 Core Sampling Procedures

Assay intervals were determined by the author at the time of logging. The intervals, ranging from 0.5 to 2.0 meters in length, were based on a combination of alteration, mineralogy, and lithology. Core recovery was measured for each assay interval.

The core from each assay interval was split in half with a hydraulic core splitter. The splitting was done in a representative manner under the supervision of the author and there are no known biases in the samples. Half the core from each interval was double-bagged and the other half was returned to the core box for storage. Four-part tags were used to label the samples - two parts were sent to the laboratory, one part was stapled into the core box at the end of the sample interval and one part was retained in the sample book. Samples were stored in a secure location on-site and then transported directly to the laboratory by Mr. R. Whatley, a director of Alpha Gold Corp.

Duplicate samples were obtained by submitting the remaining half of the core to the laboratory with a new sample number.

11.2 Core Sample Analyses and Results

Samples were assayed at ALS Chemex Laboratories Ltd. in Vancouver, using a standard 34 element ICP package plus a 30 gram Au fire assay with an AA finish. Atomic Absorption analyses were performed on all over-limits Ag, Cu, Zn, and Pb samples. Over-limit Au samples were analyzed by a 30 gram fire assay with a gravimetric finish. A complete description of ALS Chemex analytical techniques for ICP-AES and assay procedures is presented in Appendix III and the Certificates of Analysis are attached as Appendix VI. ALS Chemex is an ISO 9002 certified laboratory.

No specific gravity determinations were made during the 2006 program.

Significant analytical results from the core sampling are presented in Table 4.

11.3 Data Verification and Results

Standards and blanks were included in the sample stream every 20 samples as a measure of quality control. The ore reference standards used were CDN-CGS-7 and CDN-CGS-10 prepared by CDN Resource Laboratories Ltd. of Delta, B.C. CDN-CGS-7 has a recommended copper concentration value of 1.01 +/- 0.07% and a recommended gold concentration value of 0.95 +/- 0.08 g/t with 95% confidence. CDN-CGS-10 has a recommended copper concentration value of 1.55 +/- 0.07% and a recommended gold concentration value of 1.73 +/- 0.15 g/t with 95% confidence. The blank used was CDN-BL2 prepared also by CDN Resource Laboratories Ltd. CDN-BL2 has a recommended gold concentration value of <0.01 g/t gold. A complete description of the origin, preparation and analysis of CDN-CGS-7, CDN-CGS-10 and CDN-BL2 is attached as Appendix V.

The results of the analyses of standard and blank samples are shown in the assay logs (Appendix I). The arithmetic mean of 20 analyses of CDN-CGS-7 was 1.00% Cu and 0.94 g/t Au with a standard deviation of 0.03% for copper and 0.06 g/t for gold. The arithmetic mean of 19 analyses of CDN-CGS-10 was 1.56% Cu and 1.75 g/t Au with a standard deviation of 0.02% for copper and 0.11 g/t for gold. Of the 39 analyses of CDN-BL2, only one was above the recommended value of <0.01 g/t gold.

Four duplicate samples from mineralized intervals were submitted to ALS Chemex. There were no check analyses of pulp or reject samples performed by other laboratories.

The author also checked the analytical results for order-of-magnitude errors by comparing them to the visual mineral estimations in the lithologic log. No such errors were detected.

The down-hole azimuth survey data were visually inspected for spurious readings caused by the presence of magnetic minerals and reflected in anomalously high magnetic field values. Any such readings were deleted from the database and replaced with the average of the reading above and below the affected reading. All changes to the original data were noted on the survey logs.

The collar latitude and longitude survey data were checked for major errors by visually cross-referencing their plotted location with other mapped features. No errors were detected.

11.4 Reclamation

Upon completion of each hole the drill site was contoured using an excavator and seeded by hand with a roadside vegetation mix containing 20% Creeping Red Fescue, 20% Annual Ryegrass, 10% Perennial Ryegrass, 5% Kentucky Bluegrass, 18% Tall Fescue, 5% Orchard-grass, 10% Timothy, 2% White Clover, and 10% Single Cut Red Clover with the legumes inoculated. Felled timber around the site was limbed, lopped and either scattered or buried.

Felled timber along drill access trails was limbed, lopped and scattered and any exposed soil was seeded with the roadside vegetation mix. Water-bars were installed on the trails where appropriate.

All core boxes were labeled with metal tags, cross-stacked on logs pads, covered with plywood, and wrapped with chicken wire. Split boxes were stacked separately for easier access. The 2006 core is stored on-site at the old Takla Silver Mine entrance.

TABLE 4								
2006 DIAMOND DRILLING RESULTS								
DDH ID	FROM (m)	TO (m)	Length* (m)	Au (g/t)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
GD Zone								
LD06-01	180.3	180.8	0.5	6.46	40.7	0.16		0.13
LD06-23	9.1	20.3	11.2	0.375	9.2			2.44
LD06-24	19.8	21.5	1.7	0.104	5.3			2.00
LD06-24	38.2	38.8	0.6	1.465	89.4			9.86
LD06-25	70.1	71.6	1.5	0.053	14.5			1.39
Number 4B								
LD06-26	221.2	221.5	0.3	3.870	23.2			10.50
LD06-27	82.0	83.3	1.3	1.095	31.7	0.13		
Canyon Creek Skarn Zone								
LD06-05	94.4	96.2	1.8	1.060	19.8	0.83		5.28
LD06-05	113.0	127.1	14.1	1.099	23.5	0.67		0.29
including	113.0	119.5	6.5	1.960	43.5	1.20		0.55
LD06-05	160.8	162.6	1.8	1.890	70.3	2.03		
LD06-06	145.4	160.6	15.2	0.631	14.2	0.72		
LD06-07	110.8	115.7	4.9	2.502	64.1	2.45		2.88
LD06-07	136.3	146.4	10.1	1.523	33.2	0.98		
LD06-08	99.4	100.9	1.5	1.876	32.6	1.01		
LD06-08	108.7	110.3	1.6	0.942	46.7	1.55		0.11
LD06-08	152.1	154.2	2.1	4.765	174.6	4.71		0.19
LD06-12	187.6	207.3	19.7	1.450	27.7	1.81		
including	190.1	201.4	11.3	1.703	36.1	2.41		
LD06-13	261.2	278.3	17.1	0.448	16.0	0.47		
including	270.4	272.6	2.2	1.646	58.6	1.72		
LD06-14	79.8	94.1	14.3	0.585	13.3	0.57		
including	89.9	94.1	4.2	1.126	26.0	1.03		
LD06-14	112.8	114.0	1.2	2.660	10.3			1.63
LD06-14	124.1	127.1	3.0	0.600	74.5	0.62		1.78
LD06-15	88.4	97.4	9.0	0.345	6.5	0.52		
LD06-15	104.3	107.3	3.0	0.363	6.6	0.48		
LD06-15	282.1	289.0	6.9	0.918	11.8	0.80		
LD06-16	344.4	363.1	18.7	0.873	13.5	2.12		
LD06-17	422.2	457.7	35.5	0.615	8.5	0.84		
Including	422.2	425.4	3.2	0.821	15.0	1.90		
including	438.3	440.8	2.5	0.881	11.4	1.43		
including	453.9	457.7	3.8	3.381	39.6	3.23		
LD06-18	347.9	361.7	13.8	1.984	46.9	2.17		
LD06-29	162.3	167.3	5.0	0.609	5.8	0.44		
Valley Zone								
LD06-31	89.0	105.8	16.8	0.443				
LD06-32	121.0	128.6	7.6	0.501				

* the relationship between core interval length and true width is unknown

11.5 Diamond Drilling Results: Canyon Creek Skarn Zone

- **LD06-05** intersected variably mineralized skarn and massive sulfides with minor limestone from 94.4 to 162.6 metres. The skarn hangingwall, with local patches of massive pyrite, pyrrhotite, and sphalerite, graded 1.060 g/t gold, 19.8 g/t silver, 0.83% copper and 5.28% zinc over 1.8 metres. The footwall averaged 1.890 g/t gold, 70.3 g/t silver and 2.03% copper. The interval from 113.0 to 127.1, including two massive sulfide bands, graded 1.099 g/t gold, 23.5 g/t silver, and 0.67% copper including 6.5 metres grading 1.960 g/t gold, 43.5 g/t silver and 1.20% copper.
- **LD06-06** cored dominantly prograde skarn from 145.4 to 175.9 metres. The interval from the hangingwall to 160.6 metres contains chalcopyrite as local patches and interstitial to garnet grains and graded 0.631 g/t gold, 14.2 g/t silver and 0.72% copper.
- **LD06-07** encountered variably mineralized skarn from 107.9 to 146.4 metres intruded by a monzonite dyke from 115.7 to 120.9 metres. The interval from the hangingwall to 115.7 metres graded 2.502 g/t gold, 64.1 g/t silver, 2.45% copper and 2.88% zinc while an interval from 136.3 to 146.4 metres averaged 1.523 g/t gold, 33.2 g/t silver and 0.98% copper. The mineralized intervals contain chalcopyrite as local patches, blebs and interstitial to garnet grains.
- **LD06-08** contains three skarn bands with minor massive sulfide between 99.4 and 154.2 separated by sections of siliceous phyllite and limestone and intruded by a monzonite dyke from 141.0 to 152.1 metres. The interval from 99.4 to 100.9 averaged 1.876 g/t gold, 32.6 g/t silver and 1.01 g/t copper; the interval of skarn from 108.7 to 110.3, separating sections of phyllite and limestone, graded 0.942 g/t gold, 46.7 g/t silver and 1.55% copper; and the interval from 152.1 to the footwall graded 4.765 g/t gold, 174.6 g/t silver and 4.71% copper. Chalcopyrite mineralization occurs as blebs, local massive patches/bands and interstitial to garnet grains in all three intervals.
- **LD06-12** cored variably mineralized prograde skarn and minor massive sulfide from 187.6 to 211.0 metres. Chalcopyrite occurs as local massive patches and interstitial to garnet grains. The interval from 187.6 to 211.0 averaged 1.450 g/t gold, 27.7 g/t silver, and 1.81% copper.
- **LD06-13** was drilled to test the down-dip continuity of mineralization intersected in LD06-12. The hole encountered variably mineralized prograde skarn and occasional massive pyrite/pyrrhotite bands/patches from 223.9 to 290.2 metres. Chalcopyrite occurs as small blebs in the skarn and in massive pyrrhotite. The best interval graded 0.448 g/t gold, 16.0 g/t silver and 0.47% copper from 261.2 to 278.3 metres including 1.646 g/t gold, 58.6 g/t silver and 1.72% copper from 270.4 to 272.6. A massive pyrite/pyrrhotite band at the skarn footwall assayed 1.415 g/t gold, 56.5 g/t silver, and 0.80% copper over 1.9 metres.
- **LD06-14** cut two mineralized skarn and incipiently developed skarn bands between 20.6 and 128.0: an interval containing skarn, mafic tuff, and biotite hornfelsed siliceous phyllite from 79.8 to 94.1 averaged 0.585 g/t gold, 13.3

g/t silver and 0.57% copper including 1.126 g/t gold, 26.0 g/t silver and 1.03% copper from 89.9 to 94.1; a second interval from 124.1 to 127.1 returned 0.600 g/t gold, 74.5 g/t silver, 0.62% copper and 1.78% zinc.

- **LD06-15** intersected three moderately mineralized bands in prograde and retrograde skarn between 88.4 and 307.1: the interval from the hangingwall to 97.4 assayed 0.345 g/t gold, 6.5 g/t silver and 0.52% copper; the interval from 104.3 to 107.3 graded 0.363 g/t gold, 6.6 g/t silver, 0.48% copper; the interval from 282.1 to 289.0 returned 0.918 g/t gold, 11.8 g/t silver, and 0.80% copper. Chalcopyrite occurs as patches and/or blebs in all three intervals.
- **LD06-16** encountered strongly mineralized garnet-clinopyroxene-calcite prograde skarn from 344.4 to 363.1 with chalcopyrite as patches. The interval averaged 0.873 g/t gold, 13.5 g/t silver and 2.12% copper including 0.9 metres of unmineralized dyke.
- **LD06-17** was drilled to test the down-dip continuity of mineralization encountered in LD06-16. The hole cored variably mineralized garnet-clinopyroxene-calcite prograde skarn with chalcopyrite as local patches and interstitial to garnet grains from 422.2 to 457.7. The entire interval averaged 0.615 g/t gold, 8.5 g/t silver and 0.84% copper and included three higher grade intervals: 0.821 g/t gold, 15.0 g/t silver, and 1.90% copper from the hangingwall to 425.4; 0.881 g/t gold, 11.4 g/t silver and 1.43% copper from 438.3 to 440.8; and 3.381 g/t gold, 39.6 g/t silver, and 3.23% copper from 453.9 to the footwall.
- **LD06-18** was drilled to test the up-dip continuity of mineralization encountered in LD06-16. The hole encountered strongly mineralized garnet-clinopyroxene-calcite prograde skarn and mafic tuff with incipient skarn from 347.9 to 361.7. The interval contained chalcopyrite as massive bands/patches, blebs, and interstitial to garnet grains and graded 1.984 g/t gold, 46.9 g/t silver, and 2.17% copper.
- **LD06-29** cored numerous bands of generally unmineralized garnet-calcite+/-clinopyroxene prograde skarn from 162.5 to the end of the hole. The best intersection graded 0.609 g/t gold, 5.8 g/t copper and 0.44% copper from 162.3 to 167.3. Due to equipment limitations, the hole ended in skarn and therefore failed to test the footwall zone.

11.6 Diamond Drilling Results: GD Zone

- **LD06-23** was drilled underneath the oxide zone discovered in trench LTR06-03. The hole encountered bands and/or patches of massive pyrite-sphalerite –arsenopyrite in limestone from 9.1 to 20.3 metres. The sub-interval from 16.6 to 20.3 was strongly oxidized and marked by very poor core recovery (32%). The entire interval averaged 0.375 g/t gold, 9.2 g/t silver and 2.44% zinc over 11.2 metres.
- **LD06-24** was drilled to test the down-dip extension of the mineralized zone in LD06-23. The hole encountered two mineralized bands: from 19.8 to 21.5

the weakly mineralized phyllite assayed 0.104 g/t gold, 5.3 g/t silver and 2.00% zinc; and the massive pyrrhotite-sphalerite-arsenopyrite from 38.2 to 38.8 returned 1.465 g/t gold, 89.4 g/t silver and 9.86% zinc.

- **LD06-25** was drilled to further test the down-dip extension of mineralization in holes LD06-23 and LD06-24. From 11.7-71.6 the hole encountered veins with variable amounts of calcite-pyrite-sphalerite-galena-arsenopyrite in limestone. The interval from 70.1-71.6 assayed 0.053 g/t gold, 14.5 g/t silver and 1.39% zinc.

11.7 Diamond Drilling Results: Number 4B Zone

Three holes were drilled to test for the down-dip extension of the 4B Zone and to test for a mineralized antiformal closure west of the 4B. There were no significant intersections in LD06-28.

- **LD06-26** intersected a sequence of limestone, mafic tuff and argillite. A massive pyrite-sphalerite-arsenopyrite vein(?) from 221.2 to 221.5 grading 3.870 g/t gold, 23.2 g/t silver and 10.50% zinc. A zone of massive pyrite and weakly mineralized argillite from 6.8 to 10.7 metres averaged 0.258 g/t gold, 3.1 g/t silver and 0.14% zinc.
- **LD06-27** encountered massive pyrrhotite-pyrite and weakly mineralized argillite over 1.3 metres from 82.0 to 83.3 metres. The interval averaged 1.095 g/t gold, 31.7 g/t silver and 0.13% copper.

11.8 Diamond Drilling Results: Valley Zone

- **LD06-30** was drilled to follow-up the native copper observed in LRC06-07. The hole intersected very weak cinnabar-native copper mineralization in ash tuff from 97.2 to 103.1 metres. A 1.5 metre interval from 99.0 to 100.5 returned 0.12% copper.
- **LD06-30** was drilled to follow-up the gold assay results from LRC06-23. The hole intersected 16.8 metres from 89.0 to 105.8 metres averaging 0.443 g/t gold including 2.600 g/t gold from 89.0 to 90.5 metres. The anomalous gold occurs in limestone without visible mineralization, alteration, or anomalous levels of other elements.
- **LD06-31** was also drilled to follow-up LRC06-23. The hole cored 0.501 g/t gold over 7.6 metres from 121.0 to 128.6 metres including 1.865 g/t gold from 121.0 to 122.5 metres. As in LD06-31, the gold values were hosted in limestone without visible mineralization, alteration or anomalous levels of other elements.

12. REVERSE CIRCULATION DRILLING

The reverse circulation (RC) drilling program utilized a track-mounted drill under contract from Drift Exploration Drilling of High River, Alberta. The drilling was conducted mainly as a bedrock mapping tool in an area of extensive overburden cover centered on the historic Takla-Bralorne Mercury Mine. The holes were drilled approximately 100 metres apart along east-west lines at 400 metre spacing.

Access to the drill sites was via the Silver Creek Road which branches off the Fall-Tsayta Forest Service Rd. at kilometer 25. New access trails off the Silver Creek Rd. were constructed using a Cat 322 excavator under contract with Hat Lake Logging Ltd. of Fort. St. James, B.C.


In total, 3 054.1 metres of overburden and rock were drilled in 24 holes and 1 637 rock chip samples were taken for analysis during the period between July 22 and August 29, 2006. All holes were drilled at -90° inclination. Collar locations for these boreholes are plotted on Figure 6. Representative chip samples for each 1.5 metre (5 foot) interval were logged for lithology and mineralization by Daryl J. Hanson, P.Eng. All lithologic, assay, and survey logs are compiled and presented in Appendix II.

Upon completion of each hole, the collar was marked with a labeled pole. Drill-hole collars and new access trails were surveyed by Nex Tech of Fort St. James using a GPS system operating in differential mode. In this mode, precision of the UTM location was determined to be less than 3.0 meters. A summary of survey information, including UTM collar co-ordinates, collar elevation, and total depth is presented in Table 5. Elevations for some of the holes are not reported due to inconsistencies in the data.

12.1 Chip Sampling Procedures


Bedrock in the holes was sampled continuously in 1.5 metre (5 foot) increments by randomly selecting approximately 3 kilograms of chips from the drill cyclone. The sample material was bagged in a "Hubco" cloth bag and labeled with the hole number and footage interval. The sampling was done under supervision of the author and although it was not possible to rigorously collect a representative sample, there are no known biases in the samples.

Samples were air-dried on site then rice bagged and stored in a secure location on-site until they could be transported to the laboratory by Mr. R. Whatley, a director of Alpha Gold Corp.



SCALE 1:10,000

Kilometers



Lust Dust Project - 2006 Drilling

24 Apr 07

TABLE 5					
2006 RC DRILL HOLE SUMMARY DATA					
DDH-ID	UTM E	UTM N	ELEVATION (m)	LENGTH (m)	INCLINATION
LRC06-01	349026.3	6161877.6	N/R	152.4	-90
LRC06-02	349100.1	6161857.2	N/R	153.9	-90
LRC06-03	349200.6	6161844.8	N/R	103.6	-90
LRC06-04	349009.3	6161310.1	N/R	132.6	-90
LRC06-05	349058.3	6161305.0	N/R	152.4	-90
LRC06-06	349208.6	6161343.3	N/R	153.9	-90
LRC06-07	349264.3	6161330.2	N/R	152.4	-90
LRC06-08	349220.0	6161308.4	N/R	147.8	-90
LRC06-09	349018.8	6160945.5	N/R	76.2	-90
LRC06-10	349064.6	6160974.0	N/R	76.2	-90
LRC06-11	349167.6	6160940.6	1099.5	74.7	-90
LRC06-12	349270.1	6160915.8	1089.0	152.4	-90
LRC06-13	349365.9	6160917.4	1087.4	152.4	-90
LRC06-14	349061.9	6160538.5	1124.1	152.4	-90
LRC06-15	349152.0	6160542.7	1103.2	152.4	-90
LRC06-16	349346.6	6160522.3	1073.3	152.4	-90
LRC06-17	349437.8	6160515.8	1069.1	152.4	-90
LRC06-18	349283.3	6160115.7	1089.4	132.6	-90
LRC06-19	349387.5	6160123.0	1077.1	97.5	-90
LRC06-20	349480.0	6160111.1	N/R	74.7	-90
LRC06-21	349266.7	6159717.4	1059.2	153.9	-90
LRC06-22	349351.0	6159723.0	1053.9	152.4	-90
LRC06-23	349552.9	6159743.1	1054.9	76.2	-90
LRC06-24	349448.8	6159719.4	1055.1	76.2	-90
24 holes				3,051.1 m	

N/R - elevation not reported due to inconsistent data (re-survey required)

12.2 Chip Sample Analyses and Results

Samples were assayed at ALS Chemex Laboratories Ltd. in Vancouver, using a standard 34 element ICP package plus a 30 gram Au fire assay with an AA finish. A complete description of ALS Chemex analytical techniques for ICP-AES and assay procedures is presented in Appendix IV and the Certificates of Analysis are attached as Appendix VII. ALS Chemex is an ISO 9002 certified laboratory.

Significant analytical results from the chip sampling are presented in Table 6.

12.3 Data Verification

Data verification for the reverse circulation drilling program consisted of 27 duplicate samples used to provide a check on the sampling technique. These samples were collected in the same manner as the original samples and were submitted to ALS Chemex for analysis. The analytical results for the duplicate samples are presented in the assay log (Appendix II).

There were no analyses of pulps or rejects performed by other laboratories.

The collar latitude and longitude survey data were checked for major errors by cross-referencing their plotted location with other mapped features. No errors were detected.

TABLE 6 SIGNIFICANT RC DRILLING RESULTS 2006								
RCH ID	FROM (m)	TO (m)	Length* (m)	Au (g/t)	As ppm	Cu ppm	Hg ppm	Zn ppm
LRC06-07	96.0	99.1	3.1			4125		
LRC06-08	76.2	85.3	9.1	0.073	1120	264	41	
LRC06-09	15.2	21.3	6.1		2642			
LRC06-15	141.7	152.4	10.7				93	
LRC06-23	70.1	76.2	6.1	13.688				
LRC06-24	13.7	32.0	18.3		264		1054	

* the relationship between interval length and true width is unknown

12.4 Reclamation

Upon completion of each line of holes, the drill sites and access trails were seeded by hand with a roadside vegetation mix containing 20% Creeping Red Fescue, 20% Annual Ryegrass, 10% Perennial Ryegrass, 5% Kentucky Bluegrass, 18% Tall Fescue, 5% Orchard-grass, 10% Timothy, 2% White Clover, and 10% Single Cut Red Clover with the legumes inoculated.

The reclamation of drill sites and access trails was incomplete at the end of the season. The limbing, lopping and scattering of felled timber is approximately 40% complete and all trails require re-contouring by excavator.

12.5 Reverse Circulation Drilling Results

The reverse circulation drilling encountered a sequence of limestone and argillite belonging to the Permo-Triassic Cache Creek Group that have been cross-cut by splays of the Pinchi Fault system. The fault splays contain intrusions of chlorite-talc altered ultramafic rocks and bound panels of hematite-rich tuffs of unknown age. Rare felsite dykes cross-cut the stratigraphy near the southern end of the area drill tested.

- **LRC06-07** encountered maroon, hematitic ash tuff with minor sericite and chlorite alteration(?). The 3.1 metre interval from 96.0 to 99.1 metres contains native copper and grades 4125 ppm copper.
- **LRC06-08** intersected a 9.1 metre wide zone of hematitic ash tuff with anomalous metal values from 76.2 to 85.3 metres. This interval, in the hangingwall of the limestone-ash contact (fault?), averaged 0.073 g/t gold, 1120 ppm arsenic, 264 ppm copper and 41 ppm mercury. No mineralization was observed.
- **LRC06-09** intersected medium grey limestone with minor amounts of yellow oxide mineralization. The 6.1 metre interval from 15.2 to 21.3 metres averaged 2642 ppm arsenic.
- **LRC06-15** averaged 93 ppm mercury over 10.7 metres from 141.7 to 152.4 metres (end of hole). The interval is hosted by medium grey limestone without visible mineralization.
- **LRC06-23** returned 13.688 g/t gold over a 6.1 metre interval of limestone from 70.1 to 76.2 metres (end of hole). No mineralization was observed in the interval.
- **LRC06-24** intersected medium grey limestone with 18.3 metres averaging 264 ppm copper and 1054 ppm mercury from 13.7 to 32.0 metres. The interval contains 5-80% orange oxide.

13. BEDROCK TRENCHING

Three excavator trenches totaling 169 metres in length were dug to expose bedrock in an area of anomalous zinc-arsenic soil geochemistry north of the Number 3 Extension Zone and east of the Number 4B Zone. The trenches were oriented in an approximate east-west direction - approximately perpendicular to the strike of the bedding.

The trenches were located by chain and compass from the most proximal surveyed drill hole. Trench locations are summarized in Table 7 and plotted in Figure 7.

Trenches were mapped and sampled under the supervision of Daryl J. Hanson, P.Eng. Thirty (30) channel samples and three (3) grab samples were collected for analysis.

TABLE 7				
2006 TRENCH LOCATION SUMMARY DATA				
TRENCH-ID	UTM E	UTM N	LENGTH (m)	AZIMUTH
LTR06-01	347385	6161552	46	~090
LTR06-02	347374	6161677	69	~090
LTR06-03	347359	6161619	54	~090
3 trenches			169 m	

13.1 Sampling Procedures

Mineralized and oxidized bedrock in the trenches was channel sampled continuously in increments ranging from 0.4 to 1.5 metres as determined by geology. The sample material was double plastic bagged and labeled with a sample tag number. There are no known biases in the samples.

Samples were rice bagged and stored in a secure location on-site until they could be transported to the laboratory by Mr. R. Whatley, a director of Alpha Gold Corp.


13.2 Sample Analyses and Results

Samples were assayed at ALS Chemex Laboratories Ltd. in Vancouver, using a standard 34 element ICP package plus a 30 gram Au fire assay with an AA finish. A complete description of ALS Chemex analytical techniques for ICP-AES and assay procedures is presented in Appendix IV and the Certificates of Analysis are attached as Appendix VIII. ALS Chemex is an ISO 9002 certified laboratory.


Significant analytical results from the sampling are presented in Table 8.

13.3 Data Verification

There was no program of independent data verification for the bedrock trenching program.



SCALE 1:5,000
Kilometers



Lust Dust Project - 2006 Drilling

24 Apr 07

TABLE 8							
SIGNIFICANT BEDROCK TRENCHING RESULTS 2006							
LTR ID	Sample	Length*	Au	Ag	Cu	Pb	Zn
	Type	(m)	(g/t)	(g/t)	%	%	%
LTR06-01	channel	4.5	5.176	18.9			3.08
LTR06-02	channel	8.0	1.990	39.0			1.83
LTR06-02	channel	2.8	5.642	32.1			4.29
LTR06-02	channel	2.0	0.583	41.2			1.93
LTR06-02	grab		5.210	16.0			4.04
LTR06-02	grab		1.500	2210.0		22.3	1.14
LTRC06-03	channel	10.3	2.054	26.4	0.13		2.11

13.4 Reclamation

Upon completion of the sampling, the trenches were backfilled to a safe and stable condition with the exception of LTR06-01. All trees were limbed, lopped and scattered by hand.

In order to complete the reclamation, the trenches and interconnecting trails require re-contouring and seeding. LTR06-01 requires backfilling.

13.5 Bedrock Trenching Results

Trenching a coincident gold-arsenic soil geochemistry anomaly north of the Number 3 Zone resulted in the discovery of the GD Zone. The trenches uncovered sulfide and oxide mineralization across significant widths over a strike length of 100 metres.

- **LTR06-01:** LTR06-01 uncovered discontinuous bands and patches of red oxide within massive grey limestone. The oxide-limestone contacts range from sharp to gradational with oxides on fractures within limestone. Locally the oxides appear to be structurally controlled.

An irregular band of bright red oxide with “knife-edge” contacts at the west end of the trench averaged 5.176 g/t gold, 18.9 g/t silver and 3.08% zinc over a sampled length of 4.5 metres. The band appears to be a recumbently folded layer.

At the east end of the trench, a four metre wide zone of mixed oxide and limestone occupies the hangingwall of a fault oriented at 030°/40NW. The upper contact is gradational to massive grey limestone with oxides on fractures.

A 0.4 metre wide oxide zone with fault gouge oriented of 044°/90 is also exposed in the trench.

- **LTR06-02:** LTR06-02 uncovered a thirty seven metre long zone of fairly continuous red and yellow oxide in massive grey limestone. The oxide averaged 1.990 g/t gold, 39.0 g/t silver and 1.83% zinc over a discontinuous length of 8.0 metres. A grab sample of yellow oxide returned 1.500 g/t gold, 2210 g/t silver, 22.3% lead and 1.14% zinc.

A band of massive arsenopyrite and sphalerite was exposed at the limestone-phyllite contact at the west end of the trench. The band trends at 140° (dip not observed) and varies from 2.0 to 2.8 metres in true width. The phyllite is foliated with an orientation of 000°/68W.

A 2.8 metre channel sample of massive sulfide averaged 5.642 g/t gold, 32.1 g/t silver and 4.29% zinc. A 2.0 metre channel sample averaged 0.583 g/t gold, 41.2 g/t silver and 1.93% zinc. A single grab sample returned 5.210 g/t gold, 16.0 g/t silver and 4.04% zinc.

- **LTR06-03:** LTR06-03 exposed 10.3 metres of red and minor yellow oxide separated by 2.5 metres of massive grey limestone. The oxide zone averaged 2.054 g/t gold, 26.4 g/t silver and 2.11% zinc over the entire 10.3 metres.

14. INTERPRETATION AND CONCLUSIONS

The 2006 exploration program added significantly to the geological understanding and mineralized potential of the Lustdust property:

1. Trenching and diamond drilling a coincident gold-arsenic soil geochemistry anomaly north of the Number 3 Extension Zone resulted in the discovery of the GD Zone. The zone consists of sulphide and oxide mineralization across significant apparent widths over a strike length of 100 metres. The zone remains open to the north but persists to depth only locally. The zone is interpreted as the un-eroded remnant of a gold-silver-zinc manto similar to the Number 3 and 4B Zones. The zone has limited depth potential.
2. Drilling on the Canyon Creek Skarn Zone (holes LD06-16, LD06-17, LD06-18 and LD06-12) has proven the down-dip and along strike continuity of the high grade gold-copper-silver mineralization.
3. Drill-hole deviation creates serious problems related to the geological interpretation and resource estimate of the mineralized bands in the Canyon Creek Skarn Zone. Down-hole surveys have shown that holes can deviate as much as 150 metres from their planned trajectory. Holes drilled prior to 2002 have no down-hole survey data and therefore the location of their mineralized intersections is unknown with sufficient accuracy to allow construction of meaningful geological cross-sections.
4. The calculation of a NI43-101 compliant “inferred geological resource” is possible for the Canyon Creek Skarn Zone with the current data. Underground drilling is required in order to calculate a “drill indicated geological resource”.
5. Skarn contacts are alteration boundaries that can cross lithologic contacts. Therefore, skarn contacts should not be interpreted as being folded when drawing cross-sections.
6. The presence of gold in an otherwise un-mineralized sedimentary host rock (limestone), the mercury and arsenic trace element association, and the spatial relationship with the skarn and manto mineralization, are all indicators of the potential to discover a sediment-hosted gold deposit in the Valley Zone.
7. The linear arrangement of the Canyon Creek Skarn, the Number 3 and Number 4B Mantos, the Takla-Silver Vein and the Valley sediment hosted gold may indicate a previously unrecognized structural control to the Lustdust mineralization.
8. Drilling to the west of the 4B Zone failed to intersect significant mineralized zones either down-dip or in antiformal closures.

15. RECOMMENDATIONS

The results of the 2006 exploration warrant a 2007 exploration program as follows:

1. The Number 3 Oxide Zone requires additional drilling at depth to the north-northwest of LD04-18 and to the south-southeast of DDH 03-30. To improve recovery, future drilling of this zone should experiment with a combination of different polymers and with thin kerf NQ2 bits to penetrate faster with less water and fewer cuttings. The use of a hydraulic drill and a 5 ft. core barrel is also recommended. (Note: This work is a carryover from the 2005 recommendations. The work was not undertaken in 2005 or 2006 due to unavailability of equipment.)
2. The copper-silver soil geochemistry anomaly at the north end of the Glover Stock on the Dream Creek Grid should be drill-tested. (Note: This recommendation is also a carryover from 2005.)
3. A program of systematic 1:2500 scale mapping in conjunction with induced polarization geophysics and soil geochemistry is recommended for mineral tenure 514106, 533018, 545682 and 545684 to explore for sediment hosted gold on the west side of the Pinchi Fault and for porphyry copper-gold mineralization on the east side. Anomalous results should be followed-up with diamond drilling.
4. Based on the results from the Valley Zone, an extensive diamond drilling program is warranted to trace the gold mineralization along strike and down-dip.
5. No further surface drilling is recommended for the Canyon Creek Skarn Zone at this time. A computer model of the mineralized zone should be created from the existing database. The model would then form the basis of a NI-43-101 inferred resource estimate and would also be used to locate gaps where additional drilling is required.
6. Based on the results from previous drilling, a program of diamond drilling to explore the porphyry molybdenum potential of the Glover Stock is warranted.

The costs to complete the recommended exploration program are estimated as follows (all figures in Canadian dollars):

1. 9,000 m of NQ drilling	\$960,000
2. 50 km Induced Polarization	\$80,000
3. 50 km soil and rock geochemistry	\$50,000
4. 50 km linecutting	\$80,000
5. Assaying	\$90,000
6. Geological (mapping, core logging, reporting)	\$70,000
7. Sampling	\$18,000
8. Data-base upgrade	\$10,000
9. Road construction, environmental studies and reclamation	\$80,000
10. contingencies, transportation and management	\$60,000
11. Camp and logistical costs	\$90,000
12. Computer modeling and NI 43-101 inferred resource estimation	\$65,000
	<hr/>
Total:	\$1,653,000

16. 2006 EXPLORATION PROGRAM EXPENDITURES

1.	Diamond drilling 6,855.1 metres @ \$103/m (all inclusive cost)	\$706,075
2.	RC Drilling 3,054.1 metres @ \$57/m (all inclusive cost except camp)	\$174,084
3.	Geochemical Analyses (including transportation) 2,905 samples @ \$30/sample	\$87,150
4.	Transportation 1 - 4X4 pickup truck 100 days @ \$90/day including fuel	\$9,000
5.	Alpha camp cost 414 person days @ \$100/day Atco trailer rental (all inclusive)	\$41,400 \$20,000
6.	Drill site preparation, access construction, reclamation, and trenching (Cat 322 excavator) 352.5 hrs @ \$145.00/hr plus move and demove	\$54,565
7.	Field Wages D. Hanson - Geologist 94.5 days @ \$450/day E. Hopson - core splitting 89.5 days @ \$175.50/day D. Beausejour - labour 61.5 days @ \$175.50/day B. Elliott - core splitting 15 days @ \$175.50/day	\$42,525 \$15,797 \$10,793 \$2,532
8.	Miscellaneous field costs	\$10,069
9.	Report D. Hanson - Geologist 20 days @ \$500/day	\$10,000
		<hr/>
	TOTAL	\$1,183,990

17. REFERENCES

- ALBINO, G.V. (1987):** The Pinchi Mercury Belt, central British Columbia: near-surface expression of a Mother Lode-type mineralized system. *Geological Society of America, Abstracts with Programs*, **19:7**, A141-142.
- BUTLER, D. B., & JARVIS, K.D.G. (2000):** Report on the 2000 Magnetometer survey over the LustDust Property. Whytecliff Geophysics Ltd. Report to Alpha Gold Corp., July 14, 2000, 11p.
- DUNN, K.P.E. and RAY, G.E. (2002):** Constraints on fluid evolution at the Polymetallic Lustdust Porphyry-Skarn-Manto-Vein prospect, North Central British Columbia. British Columbia Ministry of Energy and Mines, Geological Fieldwork 2001, Paper 2002-1, pages 281 – 302.
- EINAUDI, M.T., MEINERT, L.D., AND NEWBERRY, R.J. (1981):** In Skarn Deposits. *In Economic Geology 75th Anniversary Volume*. (B.J. Skinner, ed.) *Econ. Geol. Pub. Co.*, El Paso, TX. 317-391
- EVANS, G. (1996):** Exploration of the Lustdust Property, Geology and Geochemical Report. Teck Corp. 18.
- EVANS, G. (1997):** Diamond Drilling and Geochemical Report on the 1997 Exploration of the Lustdust property. Teck Corp. 16.
- GABRIELESE, H., AND YORATH, C.J., eds. (1992):** Geology of the Cordilleran Orogen in Canada. *Geological Society of America, DNAG G-2*, 875.
- GRAF, A. (1997):** *Geology and porphyry-style mineralization of the Cerro de la Gloria stock associated with high-T, carbonate-hosted Zn-Cu-Ag (Pb) skarn mineralization, San Martin District, Zacatecas, Mexico*. Unpubl. M.S. thesis, University of Arizona, Tucson, Arizona, 123p.
- HANSON, D.J. (2005):** 2004 Diamond Drilling and Soil Geochemistry Program, Lustdust Property, Omineca Mining Division, British Columbia, Canada.
- HEDENQUIST, J.W. and ARRIBAS, A., Jr. (1999):** Epithermal gold deposits: I. hydrothermal processes in intrusion-related systems, and II. Characteristics, examples and origin of epithermal gold deposits, in Molnar, F., Lexa, J. and Hedenquist, J.W. (eds.) *Epithermal Mineralization of the Western Carpathians: Society of Economic Geologists, Guidebook Series*, v. 31, p. 13-63.
- MacINTYRE, D.G., AND STRUIK, L.C. (1999):** Nechako NATMAP Project, central British Columbia 1998 Overview British Columbia Geological Survey, Geological Fieldwork 1998, paper 1999-1 (downloaded from BCGS website, August, 1999).
- MEGAW, P.K.M. (1998):** Carbonate-hosted Pb-Zn-Ag-Cu-Au replacement deposits: An exploration perspective. *In Mineralized intrusion-related skarn systems* (Lentz, D.R., ed.). *Mineralogical Association of Canada, Short Course Series* **26**, 337-358.
- MEGAW, P.K.M., BARTON, M.D., and GRAF, A. (1998):** Polyphase skarn mineralization associated with a polyphase differentiated composite intrusion, San Martin-Sabinas District, Zacatecas, Mexico. *Geological Association of Canada/Mineralogical Association of Canada (GAC/MAC) May, 1998 Meeting, Quebec, Quebec, Abstracts*, A122
- MEGAW, P.K.M., RUIZ, J., AND TITLEY, S.R. (1988):** High-temperature, carbonate-hosted, Pb-Zn-Ag massive sulfide deposits of Mexico: An overview. *Econ. Geol.* **83**, 1856-1885.

- MEGAW, P.K.M., (1999):** Report on 1999 Drilling and Geological Study of the Lustdust Property, Omineca Mining Division, British Columbia, Canada: Alpha Gold Corp, October 14, 1999, 41.
- MEGAW, P.K.M., (2000):** Report on 2000 Drilling and Geological Study of the Lustdust Property, Omineca Mining Division, British Columbia, Canada: Alpha Gold Corp, October 14, 2000, 42.
- MEGAW, P.K.M. (2001):** Report on 2001 Drilling and Geological Study of the Lustdust Property, Omineca Mining Division, British Columbia Canada, 50 pages.
- MEINERT, L.D. (1995):** Compositional variation of igneous rocks associated with skarn deposits - Chemical evidence for a genetic connection between petrogenesis and mineralization. *In* Magmas, fluids, and ore deposits (J.F.H. Thompson, ed.). *Min. Assoc. Can. Short Course Series* **23**, 401-418.
- MEINERT, L.D. (1999):** Skarns and skarn deposits: Summary and weblinks. Skarn Website. <http://www.edu:8000/~meinert/skarnhp.html>.
- MONGER, J.W.H. (1977):** Upper Paleozoic rocks of the western Canadian Cordillera and their bearing on Cordillera evolution. *Canadian Journal of Earth Science*, **14**, 1832-1859.
- MORRIS, H.T. (1968):** The Main Tintic Mining District, Utah. *In* Ore Deposits of the United States, 1933-1967 (J.D. Ridge ed.). Amer. Inst. Mining Eng. **2**, 1043-1073.
- OLIVER, J. L. (2002):** Report on 2002 Exploration and Diamond Drilling Lustdust Property. Private internal report to Alpha Gold Corp., 62 pages.
- OLIVER, J. L. (2003):** Report on 2003 Exploration and Diamond Drilling Lustdust Property. Private internal report to Alpha Gold Corp., 109 pages.
- PATERSON, I.A. (1977):** The geology and evolution of the Pinchi Fault Zone at Pinchi Lake, central British Columbia. *Canadian Journal of Earth Science*, **14**, 1324-1342.
- PRESCOTT, B. (1916):** The Main Mineral Zone of the Santa Eulalia District. *Am. Inst. Mining Eng. Trans.* **51**, 57-99.
- PRESCOTT, B. (1926):** The underlying principles of the limestone replacement deposits of the Mexican Province. *Engr. Min. Jour.* **122**, 246-253, 289-296.
- RAY, G.E. (2002):** Geological work completed at the Lustdust Property and in some surrounding areas, Central British Columbia, (093N/11W). Private internal report to Alpha Gold Corp., 24 pages.
- RAY, G.E. AND WEBSTER, I.C.L. 1997:** Skarns in British Columbia; British Columbia Ministry of Employment and Investment, Bulletin 101, 260 pages.
- RAY, G.E., AND DAWSON, K.M., 1998,** Mineralized skarns in the Canadian Cordillera, In Mineralized intrusion-related skarn systems (Lentz, D.R., ed.), *Mineralogical Association of Canada*, Short Course Series **26**, Quebec City, 1998, p. 475-518.
- RAY, G.E., WEBSTER, I.C.L., MEGAW, P.K.M., MCGLASSEN, J.A. AND GLOVER, J.K. (2002):** The Lustdust property in central British Columbia: a polymetallic zoned porphyry – skarn – manto – vein system; in Geological Fieldwork 2001, British Columbia Ministry of Energy and Mines, Paper 2002 –1 pages 257 – 280.

SANO, H., AND STRUIK, L.C. (1997): Field properties of the Pennsylvanian-Lower Permian limestones of the Cache Creek Group, northwest of Fort St. James, British Columbia. *Geological Survey of Canada, Current Research* **1997-A**, 85-73.

SCHIARIZZA, P., AND MacINTYRE, D.G. (1999): Geology of the Babine Lake-Takla Lake area, central British Columbia (93K/11,12,13,14; 93N/3,4,5,6. British Columbia Geological Survey, Geological Fieldwork 1998, paper **1999-1** (downloaded from BCGS website, August, 1999).

SCHIARIZZA, P. (2000): Bedrock geology and Mineral occurrences, Old Hogem (Western part). British Columbia Geological Survey, Open File 2000-33, scale 1:100,000.

SOREGAROLI, A. (1999): Memo on regional geological, geochemical, and geophysical studies performed in the Lustdust area by research institutions. Report to Alpha Gold Corp., October, 1999.

TITLEY, S.R. (1993): Characteristics of High temperature carbonate-hosted massive sulfide ores in the United States, Mexico and Peru. *In Mineral Deposit Modeling* (R.V. Kirkham, W.D. Sinclair, R.I. Thorpe, and J.M. Duke, eds.). *Geol. Assoc. Can. Special Paper* **40**, 585-614.

TITLEY, S.R., AND MEGAW, P.K.M. (1985): Carbonate-hosted ores of the Western Cordillera: an overview. *A.I.M.E. Preprint* **85-115**, 17p.

TITLEY, S.R., AND MEGAW, P.K.M. (1995): The setting and genesis of high-temperature, massive, carbonate-hosted replacement ores. Society of Economic Geologists International Field Conference on Carbonate-hosted Lead-Zinc Deposits, St. Louis Missouri, June 3-6, 1995, Extended Abstracts, 314-316.



18. CERTIFICATE OF AUTHOR

I, Daryl J. Hanson, P.Eng., do hereby certify that:

1. I am a consulting geologist and the sole proprietor of

In-Depth Geological Services
16575 Quick East Road
Telkwa, B.C.
Canada. V0J 2X2.
2. I hold an BAsC degree, conferred by the University of British Columbia in 1971.
3. I am a member, in good standing, of the Association of Professional Engineers and Geoscientists of British Columbia.
4. I have worked as a geologist for over thirty years in the fields of exploration, mine development and mine operations.
5. I am responsible for (subject to the points noted in the “Disclaimer”) the preparation of the report titled “**2006 Diamond Drilling and Soil Geochemistry Exploration Program, Lustdust Property, Omineca Mining Division, British Columbia, Canada**” and dated April 29, 2006 (“the Report”).
6. I worked on site at the Lustdust property for 93 days between June 24 and October 8, 2004; for 64 days between June 11 and October 2, 2005; and for 95 days between June 12 and December 9, 2006. I had no involvement with the Lustdust property prior to 2004.
7. I am not aware of any material fact or material change with respect to the subject matter of the Report that is not reflected in the Report, which the omission to disclose would make the Report misleading.
8. I have no direct or indirect interest in Alpha Gold Corp.
9. I consent to the use of the Report by Alpha Gold Corp. for any purpose including publication on their website.

Dated this 28th day of April, 2007.

Daryl J. Hanson, P.Eng.
Telkwa, British Columbia, Canada

Appendix I

2006 Diamond Drill-hole Logs

RQD Log LD06-01

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
3.1			136.2		
5.2	30	14	139.3	197	64
8.2	205	68	142.3	107	36
11.3	135	44	145.4	115	37
14.3	95	32	148.4	71	24
17.4	78	25	151.5	88	28
20.4	77	26	154.5	154	51
23.5	132	43	157.6	272	88
26.5	65	22	160.6	213	71
29.6	124	40	163.7	212	68
32.6	103	34	166.7	254	85
35.7	147	47	169.8	251	81
38.7	37	12	172.8	213	71
41.8	194	63	175.9	263	85
44.8	240	80	178.9	141	47
47.9	205	66	182.0	70	23
50.9	150	50	185.0	22	7
54.0	118	38	188.1	41	13
57.0	44	15	191.1	89	30
60.0	260	87	194.1	107	36
63.1	140	45	197.2	241	78
66.1	234	78	200.3	213	69
69.2	84	27	203.3	144	48
72.2	174	58	206.4	145	47
75.3	132	43	209.4	92	31
78.3	121	40	212.5	205	66
81.4	205	66	215.5	239	80
84.4	77	26	218.5	239	80
87.5	172	55			
90.5	104	35		EOH @ 218.5	
93.6	80	26			
96.6	82	27			
99.7	165	53			
102.7	101	34			
105.8	221	71			
108.8	232	77			
111.9	151	49			
114.9	184	61			
118.0	252	81			
121.0	188	63			
124.0	147	49			
127.1	151	49			
130.1	13	4			
133.2	222	72			
136.2	159	53			

RQD Log LD06-02

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
3.1			136.3		
5.2	65	31	139.3	136	64
8.2	134	45	142.3	155	59
11.3	205	66	145.4	198	72
14.3	181	60	148.4	176	78
17.4	151	49	151.5	222	92
20.4	123	41	154.5	234	83
23.5	200	65	157.6	284	90
26.5	175	58	160.6	250	67
29.6	254	82	163.7	280	80
32.6	132	44	166.7	202	95
35.7	122	39	169.8	247	86
38.7	132	44	172.8	284	73
41.8	209	67	175.9	268	94
44.8	252	84	178.9	220	90
47.9	266	86	182.0	292	61
50.9	173	58	185.0	270	68
54.0	128	14	188.1	188	60
57.0	98	32	191.1	205	58
60.0	71	24	194.2	187	66
63.1	108	35	197.2	175	36
66.1	132	44	200.3	205	49
69.2	180	58	203.3	107	92
72.2	173	58	206.4	152	52
75.3	152	49	209.4	277	59
78.3	220	73	212.5	160	60
81.4	225	73	215.5	177	59
84.4	214	71	218.6	185	81
87.5	215	69	221.6	177	66
90.5	180	60	224.6	242	63
93.6	205	66	227.7	205	71
96.6	168	56	230.7	190	86
99.7	213	69	233.8	220	85
102.7	255	85	236.8	257	59
105.8	238	77	239.9	264	61
108.8	170	57	242.9	176	95
111.9	167	54	246.0	188	33
114.9	183	61	249.0	285	49
118.0	84	27	252.1	103	83
121.0	148	49	255.1	147	64
124.1	186	60	258.2	256	83
127.1	83	28	261.2	193	64
130.2	247	80			
133.2	179	60		EOH @ 261.2m	
136.3	189	63			

RQD Log LD06-03

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
3.1			136.3		
5.2	72	34	139.3	77	26
8.2	113	38	142.3	177	59
11.3	55	18	145.4	115	37
14.3	0	0	148.4	236	79
17.4	50	16	151.5	215	69
20.4	10	3	154.5	247	82
23.5	10	3	157.6	211	68
26.5	20	7	160.6	225	75
29.6	50	16	163.7	245	79
32.6	28	9	166.7	148	49
35.7	65	21	169.8	282	91
38.7	15	5	172.8	252	84
41.8	11	4	175.9	231	75
44.8	47	16	178.9	288	96
47.9	225	73	182.0	248	80
50.9	226	75	185.0	228	76
54.0	228	74	188.1	227	73
57.0	169	56	191.1	213	71
60.0	236	79	194.2	197	64
63.1	140	45	197.2	219	73
66.1	241	80	200.3	253	82
69.2	143	46	203.3	269	90
72.2	164	55	206.4	259	84
75.3	173	56	209.4	264	88
78.3	228	76	212.5	222	72
81.4	223	72	215.5	75	25
84.4	144	48	218.6	191	62
87.5	112	36	221.6	165	55
90.5	210	70	224.6	181	60
93.6	240	77	227.7	170	55
96.6	260	87			
99.7	264	85		EOH @ 227.7m	
102.7	288	96			
105.8	253	82			
108.8	249	83			
111.9	180	58			
114.9	199	66			
118.0	102	33			
121.0	161	54			
124.1	202	65			
127.1	193	64			
130.2	70	23			
133.2	207	69			
136.3	188	61			

RQD Log LD06-04

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
3.1			136.3		
5.2	80	38	139.3	116	39
8.2	0	0	142.3	50	17
11.3	50	16	145.4	52	17
14.3	120	40	148.4	50	17
17.4	154	50	151.5	246	79
20.4	230	77	154.5	163	54
23.5	188	61	157.6	121	39
26.5	154	51			
29.6	140	45		EOH @ 157.6m	
32.6	15	5			
35.7	65	21			
38.7	80	27			
41.8	127	41			
44.8	77	26			
47.9	162	52			
50.9	51	17			
54.0	145	47			
57.0	61	20			
60.0	111	37			
63.1	153	49			
66.1	242	81			
69.2	159	51			
72.2	131	44			
75.3	187	60			
78.3	203	68			
81.4	169	55			
84.4	207	69			
87.5	151	49			
90.5	152	51			
93.6	249	80			
96.6	256	85			
99.7	126	41			
102.7	80	27			
105.8	121	39			
108.8	85	28			
111.9	105	34			
114.9	215	72			
118.0	56	18			
121.0	35	12			
124.1	99	32			
127.1	83	28			
130.2	26	8			
133.2	55	18			
136.3	111	36			

Diamond Drill Log

LD06-05

Date:

Logged By: DJH

Page 2/5

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
94.4	95.2	MS					2						25	15	5	20				2	Massive Sulfide
																					w/ 30% bands/patches of ca-garnet Prograde Skarn
																					upper cnt sharp, irreg
																					lower cnt gradational
																					PO/CP/SL as large patches
																					PY as cubes to 10mm
																					MG interstitial to PY cubes
																					w/ 10% calcite and patches of limestone
95.2	95.6	SKpm					4	1					10							10	Mineralized Ca-Garnet+Calcite Prograde Skarn
																					w/ 20% dk green/black chlorite Retrograde Skarn
																					PY as xtline patches
																					MG interstitial to PY cubes
																					0.5% xtline calcite
																					lower cnt gradational
95.6	96.2	SKrm					1	4					25		1					5	Mineralized Chlorite+Calcite+Epidote Retrograde Skarn
																					w/ loc patches Prograde Skarn
																					PY as granular patches/coarse cubes
																					MG interstitial to PY cubes
																					CP as blebs
																					lower cnt very irregular
96.2	99.1	LSa							5												Limestone
																					med blue/grey, massive, recrystallized
																					w/ 15% argillaceous laminae
99.1	101.6	SKp					4						2							1	Ca-Garnet+Calcite Prograde Skarn
																					w/ 10% patches of pale green/grey, fine grained chlorite?+calcite (retrograde?)
																					PY as xtline patches
																					MG as blebs w/ calcite
																					lower cnt gradational
101.6	102.9	SKr					1	4					<1								Chlorite+Calcite+Epidote Retrograde Skarn
																					w/ loc patches of ca-garnet Prograde Skarn
																					dk green/black chlorite patches; loc EP patches
																					PY as small cubes

Diamond Drill Log

LD06-05

Date:

Logged By: DJH

Page 3/ 5

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments				
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG			
102.9	113.0	LS							5				tr											Limestone blue/grey, recrystallized, wkly laminated 107.9-108.2: SL+PY+PO+CP vein? or replacement? w/ sharp, irreg cnts
113.0	113.8	MS											50		15	15								Massive Sulfides CP/SL as patches PY as xtlne patches 113.6-113.8: healed sulfide breccia w/ 50% calcite matrix; sharp, irreg cnts
113.8	119.1	SKrm					1	4	tr				60		5							1	Mineralized Chlorite+Calcite+Epidote Retrograde Skarn w/ 10% patches of ca-garnet Prograde Skarn dark green/black chlorite patches 115.1-115.4: massive PY; carbonate replacement w/ 10% limestone patches MG as loc blebs PY as patches CP as patches/blebs lower cnt not observed	
119.1	119.8	SKpm					4	1					5		2									Mineralized Ca-Garnet Prograde Skarn w/ 10% chlorite+calcite Retrograde Skarn PY as xtlne patches CP interstitial to garnet grains healed bxia at lower cnt
			LC	119.8	55																			
119.8	121.6	MS											50											Massive Sulfides PY as xtlne patches 5% HS as patches interstitial to PY 45% siliceous patches lower cnt gradational over 0.3m
121.6	127.5	SKpm					5						1		2									Weakly Mineralized Ca-Garnet Prograde Skarn w/ 10% lt grey/green, fine grained calcareous patches (retrograde alt'n?) over top 1.5m of interval CP as blebs PY as blebs HS as patches lower cnt gradational

Assay Sample Log LD06-05

Page: 1

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Zn
	0.0	94.4	no sample								
368902	94.4	96.2			1.8	100	1.060	19.8	389	8290	52800
	96.2	99.1	no sample								
368903	99.1	100.6			1.5	100	0.076	1.2	642	335	165
368904	100.6	101.6			1.0	100	0.091	0.9	175	240	170
368905	101.6	102.9			1.3	100	0.052	0.4	137	127	63
	102.9	107.9	no sample								
368906	107.9	108.2			0.3	100	0.385	22.6	26	7770	170500
	108.2	113.0	no sample								
368907	113.0	114.5			1.3	87	2.940	111.0	6400	29900	22000
368908	114.5	116.0			1.2	80	2.800	16.9	664	4580	979
368909	116.0	118.0			0.7	35	0.879	13.1	1290	4440	188
368910	118.0	119.5			1.4	93	1.580	43.0	3020	11800	524
368911	119.5	121.0			1.5	100	0.613	13.0	1305	2280	175
368912	121.0	122.5			1.5	100	0.569	7.3	593	1360	2740
368913	122.5	124.1			1.5	94	0.074	3.0	123	1575	45
368914	124.1	125.6			1.5	100	0.384	5.0	240	2990	46
368915	125.6	127.1			1.5	100	0.193	3.7	244	2150	40
368916	127.1	128.6			1.5	100	0.048	1.6	203	870	28
368917	128.6	130.2			1.6	100	0.012	0.2	174	121	23
368918	130.2	131.7			1.5	100	0.027	0.3	136	142	22
368919	131.7	132.3			0.6	100	0.046	1.6	148	454	33
	132.3	145.4	no sample								
368920			blank				0.002	0.1	4	38	41
368921			CGS-7				0.987	3.4	7	10200	81
368922	145.4	146.6			1.2	100	0.005	0.3	115	26	25
368923	146.6	147.7			0.9	82	0.059	2.0	50	1105	27
368924	147.7	149.1			1.4	100	0.050	0.4	86	217	23
368925	149.1	150.6			1.5	100	0.022	0.1	163	35	22
368926	150.6	152.1			1.5	100	0.031	0.2	171	42	19
368927	152.1	153.6			1.5	100	0.008	0.2	157	25	16
368928	153.6	155.1			1.5	100	0.042	0.1	173	6	11

RQD Log LD06-05

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
6.1			139.3		
8.2	12	6	142.3	284	95
11.3	142	46	145.4	244	79
14.3	222	74	148.4	227	76
17.4	295	95	151.5	168	54
20.4	211	70	154.5	229	76
23.5	267	86	157.6	241	78
26.5	243	81	160.6	197	66
29.6	265	85	163.7	294	95
32.6	260	87	166.7	287	96
35.7	290	94	169.8	276	89
38.7	214	71	172.8	291	97
42.8	212	52	175.9	288	93
44.8	279	140	178.9	290	97
47.9	243	78	182.0	292	94
50.9	211	70	185.0	251	84
54.0	226	73	188.1	300	97
57.0	273	91	191.1	274	91
60.1	303	98	194.2	250	81
63.1	227	76	197.2	277	92
66.2	245	79			
69.2	254	85		EOH @ 197.2m	
72.2	226	75			
75.3	167	54			
78.3	211	70			
81.4	237	76			
84.4	254	85			
87.5	200	65			
90.5	152	51			
93.6	123	40			
96.6	207	69			
99.7	184	59			
102.7	192	64			
105.8	234	75			
108.8	213	71			
111.9	224	72			
114.9	128	43			
118.0	66	21			
121.0	241	80			
124.1	258	83			
127.1	261	87			
130.2	302	97			
133.2	277	92			
136.3	259	84			
139.3	279	93			

RQD Log LD06-06

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
6.1			139.3		
8.2	119	57	142.3	212	71
11.3	169	55	145.4	270	87
14.3	183	61	148.4	286	95
17.4	244	79	151.5	253	82
20.4	209	70	154.5	125	42
23.5	207	67	157.6	257	83
26.5	214	71	160.6	286	95
29.6	216	70	163.7	280	90
32.6	258	86	166.7	241	80
35.7	212	68	169.8	234	75
38.7	300	100	172.8	318	106
42.8	253	62	175.9	254	82
44.8	273	137	178.9	275	92
47.9	263	85	182.0	262	85
50.9	266	89	185.0	288	96
54.0	273	88	188.1	272	88
57.0	258	86	191.1	297	99
60.1	269	87	194.2	303	98
63.1	215	72	197.2	260	87
66.2	211	68	200.3	230	74
69.2	296	99	203.3	285	95
72.2	271	90	206.4	290	94
75.3	244	79			
78.3	241	80		EOH @ 206.4m	
81.4	259	84			
84.4	262	87			
87.5	267	86			
90.5	267	89			
93.6	116	37			
96.6	206	69			
99.7	242	78			
102.7	167	56			
105.8	165	53			
108.8	183	61			
111.9	237	76			
114.9	158	53			
118.0	180	58			
121.0	219	73			
124.1	123	40			
127.1	12	4			
130.2	22	7			
133.2	223	74			
136.3	236	76			
139.3	218	73			

Diamond Drill Log

LD06-07

Date:

Logged By: DJH

Page 1/ 5

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
0.0	3.1	OB																			Overburden triconed - no core
3.1	78.5	SPbh				3				2		2									Biotite Hornfelses Siliceous Phyllite w/ 5-15% lt brown, biotite laminae grades loc to Sericite Altered Siliceous Phyllite w/ tan coloured alt'n of biotite PY as patches, vns, vnlt, <vnlt grades loc to siliceous argillite (dk grey/lt grey laminated qtz-muscovite phyllite) laminae locally contorted 34.3-35.8: siliceous argillite 64.0-69.0: dk grey, carbonaceous siliceous argillite grading loc to SPbh
			S1	10.2	50																
			S1	15.7	30																
			S1	21.2	60																
			S1	26.2	45																
			S1	32.2	35																
			S1	38.1	50																
			S1	43.7	35																
			S1	49.0	30																
			S1	55.2	30																
			S1	61.0	30																
			S1	67.0	20																
			S1	72.6	30																
			S1	78.0	28																
78.5	78.9	MS										40		1						5	Massive Pyritic Sulfides PY as patches CP as blebs MG as patches 15% massive, yellow, granular garnet (pyritic Prograde Skarn) 10% xtline calcite patches 35% remnant limestone (carbonate replacement) strongly broken cnts not observed
78.9	96.9	LSa							5												Limestone w/ <2% argillaceous lams blue/grey, recrystallized
96.9	97.8	SKp					4 tr		1			<1									Ca-Garnet+Calcite+Epidote Prograde Skarn w/ 10% limestone remnants massive yellow and lt brown garnets tr dk green/black retrograde chlorite patches PY as patches

Diamond Drill Log

LD06-07

Date:

Logged By: DJH

Page 2/5

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
																					96.9-97.8: cont'd cnts sharp, irregular
97.8	107.9	LSa					tr		5				<1								Limestone med blue/grey, recrystallized w/ loc patches/bands Prograde Skarn 2-10% argillaceous lams tr retrograde chlorite rims on garnets PY as cubes and patches in skarn patches/bands
107.9	110.8	SKp					5	tr					<1								Ca-Garnet+Calcite+Diopside Prograde Skarn lt yellow/green and red/brown garnets w/ 30% lt green, wkly altered diopside? patches PY as blebs upper cnt not observed lower cnt gradational
110.8	115.0	SKpm					5	tr					<1		3						Mineralized Ca-Garnet+Calcite Prograde Skarn massive yellow and lt red/brown garnet w/ 10% white xline calcite patches CP/PY as patches and interstitial to garnet grains MG as small patches (pseudos after xline HS) minor dk green/black retrograde chlorite lower cnt sharp, irreg 111.9: monzonite dyklet; 0.12m wide; w/ diffuse cnts @ 40 deg. to core axis
115.0	115.7	MS					1								5	45	35				Massive Sulfides w/ 10% ca-garnet Prograde Skarn bands CP/SL as patches PO as blebs in CP lower cnt sharp, planar
			LC	115.7	65																
115.7	120.9	Md																			Monzonite Dyke med grained, w/ 30% euhedral feldspar phenos to 3mm no alteration/mineralization upper cnt chilled loc feldspar megacrysts to 10X5mm

Diamond Drill Log

LD06-07

Date:

Logged By: DJH

Page 3/ 5

From	To	Rock	Struct	@	CA	Alteration								Mineralization								Comments
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN	MG		
																						115.7-120.9: cont'd
																						lower cnt gradational (w/o chilled margin)
																						minor endoskarn w/ EP at lower cnt
120.9	121.7	SKp					3	tr	2				<1									Incipient Ca-Garnet+Epidote Prograde Skarn
																						w/ 30% limestone remnants
																						PY as blebs
121.7	122.7	SKpm					5	tr					1	2							1	Mineralized Ca-Garnet+Calcite Prograde Skarn
																						massive yellow garnet w/ 5% xtline calcite patches
																						MG as pseudos after xtline HS
																						PY/CP interstitial to garnet grains
																						v. weak chlorite retrograde alt'n rims on garnets
122.7	131.4	SKp					5	tr					1	0.5								Weakly Mineralized Ca-Garnet+Calcite Prograde Skarn
																						massive yellow garnets w/ 5% xtline calcite patches
																						5% xtline HS patches
																						minor lt red/brown garnet
																						PY as blebs
																						CP as loc patches/blebs
																						loc. pale grey/green chlorite+clay retrograde alt'n
131.4	132.6	SKpm					5	tr					3	0.5								Weakly Mineralized Ca-Garnet+Calcite Prograde Skarn
																						massive yellow granular garnet w/ 5% xtline calcite patches
																						PY as patches to 10mm
																						CP interstitial to garnet grains
																						lower cnt gradational
																						tr dark green/black retrograde Chlorite alt'n rims on garnet grains
132.6	134.0	SKp					3	2														Ca-Garnet+Calcite+Diopside? Prograde Skarn
																						w/ 60% massive yellow garnet w/ xtline calcite patches
																						40% lt grey/green, clay+chlorite retrograde alt'n patches
																						lower cnt gradational
134.0	135.9	SKp					5	tr					tr									Ca-Garnet+Calcite Prograde Skarn
																						massive yellow garnet grains w/ 2% xtline calcite patches
																						1% xtline HS patches

Diamond Drill Log

LD06-07

Date:

Logged By: DJH

Page 4/ 5

From	To	Rock	Struct	@	CA	Alteration							Mineralization								Comments
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN	MG	
																					134.0-135.9: cont'd
																					gradational lower cnt
																					tr dark green/black retrograde chlorite alt'n rims on garnet
135.9	137.6	SKpm					5	tr				2		2						2	Mineralized Ca-Garnet+Calcite Prograde Skarn
																					a/a 121.7-122.7
																					w/ 5% xtline calcite patches
																					CP as patches and interstitial to garnet grains
																					PY as patches
																					MG as pseudos after xtline HS
137.6	138.6	SKp					5	tr				1		tr							C-Px Prograde Skarn
																					lt grey/green Prograde Skarn
																					w/ loc lt green/beige chlorite+clay retrograde alt'n
																					CP as blebs
																					PY as patches
																					loc creamy colour when pervasively clay altered
																					lower cnt gradational
138.6	140.9	SKpm					5	tr				2		2						2	Mineralized Ca-Garnet+Calcite Prograde Skarn
																					a/a 135.9-137.6
																					w/ 3% xtline calcite patches
																					CP as patches and interstitial to garnet grains
																					PY as xtline patches
																					MG as pseudos after xtline HS
																					lower cnt gradational
140.9	143.1	SKpm					4	1				tr		0.5						3	Weakly Mineralized Ca-Garnet+Diopside+Calcite Prograde Skarn
																					massive yellow granular garnet and pale green diopside?
																					w/ 3% xtline calcite patches
																					CP as blebs
																					PY as blebs
																					tr HS
																					141.4-142.0: MG+EP mineralization (retrograde alt'n?)
																					lower cnt gradational

Assay Sample Log LD06-07

Page: 1

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Zn
	To	96.9	no sample								
368958	96.9	97.8			0.9	100	0.049	1.9	160	377	72
	97.8	107.9	no sample								
368959	107.9	109.4			1.5	100	0.147	3.6	101	938	152
368960			blank				0.009	0.1	6	34	37
368961			CGS-7				0.983	3.9	2	9770	82
368962	109.4	110.8			1.4	100	0.081	3.6	137	993	171
368963	110.8	112.3			1.5	100	1.650	43.4	144	11300	279
368964	112.3	113.8			1.5	100	1.310	53.3	163	13100	289
368964	113.8	115.0			1.2	100	2.100	26.5	176	6010	151
368966	115.0	115.7			0.7	100	7.570	196.0	51	109000	200000
	115.7	120.9	no sample								
368967	120.9	121.7			0.8	100	0.055	2.8	20	554	214
368968	121.7	122.8			1.0	93	0.965	24.6	224	9100	1145
368969	122.8	124.2			1.5	108	0.078	3.2	281	1230	54
368970	124.2	125.7			1.5	100	0.147	4.6	253	1720	121
368971	125.7	127.2			1.5	100	0.073	1.3	209	500	52
368972	127.2	128.7			1.5	100	0.122	3.5	187	1580	68
368673	128.7	130.2			1.1	73	0.152	1.2	222	574	24
368974	130.2	131.7			1.5	100	0.098	2.7	157	999	38
368975	131.7	133.2			1.5	100	0.774	5.2	177	2010	34
368976	133.2	134.7			1.5	100	0.069	0.4	92	133	38
368977	134.7	136.3			1.6	100	0.022	10.8	140	2790	71
368978	136.3	137.8			1.5	100	1.220	29.3	119	7500	186
368979	137.8	139.3			1.5	100	3.200	45.8	66	13200	365
368980			blank				0.002	0.4	3	54	40
368981			CGS-10				1.805	5.3	22	15700	88
368982	139.3	140.8			1.5	100	0.595	15.6	149	4600	118
368983	140.8	142.3			1.5	100	0.482	10.5	62	3710	71
368984	142.3	143.8			1.5	100	0.467	12.5	95	3740	88
368985	143.8	145.4			1.6	100	0.579	18.8	75	5230	163
368986	145.4	146.4			1.0	100	5.510	135.0	420	41600	966

RQD Log LD06-07

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
3.1			136.3		
5.2	31	15	139.3	231	77
8.2	66	22	142.3	222	74
11.3	190	61	145.4	248	80
14.3	247	82	148.4	165	55
17.4	270	87	151.5	173	56
20.4	153	51	154.5	60	20
23.5	126	41	157.6	203	65
26.5	201	67	160.6	212	71
29.6	254	82	163.7	216	70
32.6	200	67			
35.7	222	72		EOH @ 163.7m	
38.7	262	87			
41.8	254	82			
44.8	235	78			
47.9	275	89			
50.9	206	69			
54.0	174	56			
57.0	276	92			
60.1	272	88			
63.1	250	83			
66.2	262	85			
69.2	268	89			
72.2	268	89			
75.3	209	67			
78.3	162	54			
81.4	133	43			
84.4	279	93			
87.5	234	75			
90.5	298	99			
93.6	243	78			
96.6	278	93			
99.7	267	86			
102.7	270	90			
105.8	248	80			
108.8	93	31			
111.9	215	69			
114.9	235	78			
118.0	241	78			
121.0	212	71			
124.1	221	71			
127.1	132	44			
130.2	234	75			
133.2	247	82			
136.3	217	70			

RQD Log LD06-08

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
3.1			136.3		
5.2	0	0	139.3	232	77
8.2	54	18	142.3	196	65
11.3	133	43	145.4	107	35
14.3	217	72	148.4	147	49
17.4	258	83	151.5	183	59
20.4	183	61	154.5	238	79
23.5	177	57	157.6	236	76
26.5	225	75	160.6	253	84
29.6	159	51	163.7	254	82
32.6	95	32	166.7	240	80
35.7	213	69	169.8	160	52
38.7	132	44	172.8	245	82
41.8	215	69	175.9	134	43
44.8	118	39	178.9	283	94
47.9	243	78	182.0	263	85
50.9	186	62	185.0	248	83
54.0	275	89	188.1	277	89
57.0	280	93			
60.1	260	84		EOH @ 188.1m	
63.1	229	76			
66.2	251	81			
69.2	234	78			
72.2	169	56			
75.3	258	83			
78.3	262	87			
81.4	268	86			
84.4	238	79			
87.5	231	75			
90.5	246	82			
93.6	185	60			
96.6	194	65			
99.7	247	80			
102.7	212	71			
105.8	211	68			
108.8	149	50			
111.9	202	65			
114.9	276	92			
118.0	178	57			
121.0	234	78			
124.1	83	27			
127.1	142	47			
130.2	232	75			
133.2	218	73			
136.3	227	73			

RQD Log LD06-11

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
3.1					
5.2	13	6			
8.2	140	47			
11.3	260	84			
14.3	183	61			
17.4	183	59			
20.4	260	87			
23.5	178	57			
26.5	235	78			
29.6	108	35			
32.6	211	70			
35.7	139	45			
38.7	187	62			
41.8	209	67			
44.8	262	87			
47.9	273	88			
50.9	249	83			
54.0	258	83			
57.0	224	75			
60.1	275	89			
63.1	156	52			
66.2	175	56			
69.2	149	50			
72.2	185	62			
75.3	301	97			
78.3	286	95			
81.4	219	71			
84.4	247	82			
87.5	118	38			
90.5	194	65			
93.6	145	47			
96.6	76	25			
99.7	253	82			
102.7	217	72			
105.8	73	24			
108.8	154	51			
111.9	77	25			
114.9	165	55			
118.0	254	82			
121.0	270	90			
EOH @ 121.0m					

Diamond Drill Log

LD06-12

Date:

Logged By: DJH

Page 2/ 3

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
187.6	190.1	SKpm-SKrm					2	3					10		2					5	Mixed Interval of Mineralized Prograde and Retrograde Skarn 60% dk green/black chlorite+calcite Retrograde Skarn 40% Ca-Garnet+Calcite Prograde Skarn PY as xtlne patches CP as large patch at 188.5 MG as patches/bands
190.1	191.1	MS				tr	1					5	70	10						5	Massive Sulfides w/ loc bands and patches of prograde and retrograde skarn PO as massive patches PY as xtlne patches CP as massive patches lower cnt gradational
191.1	192.4	SKpm				tr	5					4	0.3								Weakly Mineralized Ca-Garnet+Calcite Prograde Skarn PY/CP interstitial to garnet grains grades loc to Biotite Hornfelsed Siliceous Phyllite lower cnt gradational
192.4	198.4	SKpm					5	tr				2	5							1	Mineralized Ca-Garnet+Calcite Prograde Skarn 5% xtlne calcite patches; loc patches Retrograde Skarn PY/CP as patches and interstitial to garnet grains MG as patches/blebs lower cnt gradational
198.4	200.5	SKpm					5	tr				2	0.3							tr	Weakly Mineralized Ca-Garnet+Calcite Prograde Skarn 5% xtlne calcite patches w/ loc patches chlorite Retrograde Skarn PY/CP as blebs and interstitial to garnet grains loc patches of EP MG pseudos after xtlne HS lower cnt gradational
200.5	207.3	SKpm					5	tr				2	5							1	Mineralized Ca-Garnet+C-Px+Calcite Prograde Skarn yellow/green, massive garnet 5% xtlne calcite patches PY/CP as masses and interstitial to garnet grains

RQD Log LD06-12

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
5.2	0		136.3		
8.2	17	6	139.3	225	75
11.3	16	5	142.3	252	84
13.4	0	0	145.4	274	88
14.3	0	0	148.4	248	83
17.4	121	39	151.5	223	72
20.4	199	66	154.5	257	86
23.5	263	85	157.6	157	51
26.5	227	76	160.6	181	60
29.6	229	74	163.7	92	30
32.6	273	91	166.7	66	22
35.7	214	69	169.8	48	15
38.7	194	65	172.8	204	68
41.8	275	89	175.9	282	91
44.8	300	100	178.9	288	96
47.9	106	34	182.0	226	73
50.9	217	72	185.0	128	43
54.0	270	87	188.1	166	54
57.0	171	57	191.1	292	97
60.1	205	66	194.2	250	81
63.1	210	70	197.2	240	80
66.2	291	94	200.3	217	70
69.2	251	84	203.3	274	91
72.2	144	48	206.4	266	86
75.3	175	56	209.4	282	94
78.3	266	89	212.5	283	91
81.4	240	77	215.5	301	100
84.4	223	74	218.5	278	93
87.5	284	92	221.6	256	83
90.5	284	95	224.6	280	93
93.6	258	83	227.7	297	96
96.6	180	60	230.7	288	96
99.7	269	87	233.8	286	92
102.7	111	37	236.8	300	100
105.8	160	52	239.9	282	91
108.8	203	68			
111.9	261	84		EOH @ 239.9m	
114.9	228	76			
118.0	282	91			
121.0	298	99			
124.1	286	92			
127.1	272	91			
130.2	270	87			
133.2	281	94			
136.3	132	43			

Assay Sample Log LD06-13

Page: 1

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Zn
	0.0	223.9	no sample								
369032	223.9	224.6			0.6	86	0.201	1.6	17	665	30
369033	224.6	226.1			1.5	100	0.036	0.2	34	38	25
369034	226.1	227.7			1.6	100	0.110	2.4	87	60	1265
369035	227.7	229.2			1.5	100	0.095	0.1	39	19	31
369036	229.2	230.7			1.5	100	0.094	0.1	108	22	28
369037	230.7	232.2			1.5	100	0.020	0.4	32	42	38
369038	232.2	233.8			1.6	100	0.088	3.8	50	1240	58
369039	233.8	235.3			1.5	100	0.129	2.2	44	346	67
369040			blank				0.002	0.3	2	35	39
369041			CGS-7				0.912	3.6	8	9740	82
369042	235.3	236.8			1.5	100	0.076	3.1	45	855	89
369043	236.8	238.3			1.5	100	0.254	9.5	42	2910	106
369044	238.3	239.9			1.6	100	0.090	2.5	45	848	59
369045	239.9	241.4			1.5	100	0.293	7.9	58	2540	72
369046	241.4	242.9			1.5	100	0.064	0.2	137	46	14
369047	242.9	244.4			1.5	100	0.016	0.5	88	179	18
369048	244.4	246.0			1.6	100	0.014	0.1	94	27	18
369049	246.0	247.5			1.5	100	0.011	0.2	115	38	15
369050	247.5	249.0			1.5	100	0.063	0.1	30	18	25
369051	249.0	250.5			1.5	100	0.215	0.1	75	24	24
369052	250.5	252.1			1.6	100	0.017	0.1	71	30	18
369053	252.1	253.6			1.5	100	0.015	0.2	54	10	23
369054	253.6	255.1			1.5	100	0.018	0.1	41	8	21
369055	255.1	256.6			1.5	100	0.042	0.2	46	19	19
369056	256.6	258.2			1.6	100	0.015	0.1	97	27	14
369057	258.2	259.7			1.5	100	0.080	0.1	79	8	15
369058	259.7	261.2			1.5	100	0.170	2.9	73	907	32
369059	261.2	262.7			1.5	100	0.904	23.2	40	6950	140
369060			blank				0.025	0.2	3	44	41
369061			CGS-10				1.675	5.0	19	15600	79
369062	262.7	264.3			1.6	100	0.401	10.0	33	2960	112

RQD Log LD06-13

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
9.1			142.3		
11.3	0	0	145.4	273	88
14.3	162	54	148.4	208	69
17.4	217	70	151.5	274	88
20.4	253	84	154.5	300	100
23.5	255	82	157.6	282	91
26.5	277	92	160.6	221	74
29.6	2643	853	163.7	224	72
32.6	267	89	166.7	233	78
35.7	274	88	169.8	181	58
38.7	267	89	172.8	165	55
41.8	225	73	175.9	159	51
44.8	274	91	178.9	215	72
47.9	206	66	182.0	154	50
50.9	92	31	185.0	208	69
54.0	227	73	188.1	216	70
57.0	283	94	191.1	60	20
60.1	256	83	194.2	200	65
63.1	204	68	197.2	160	53
66.2	207	67	200.3	299	96
69.2	276	92	203.3	262	87
72.2	206	69	206.4	298	96
75.3	274	88	209.4	264	88
78.3	278	93	212.5	156	50
81.4	260	84	215.5	152	51
84.4	274	91	218.5	164	55
87.5	242	78	221.6	193	62
90.5	227	76	224.6	211	70
93.6	260	84	227.7	138	45
96.6	206	69	230.7	271	90
99.7	230	74	233.8	286	92
102.7	278	93	236.8	266	89
105.8	270	87	239.9	264	85
108.8	237	79	242.9	254	85
111.9	230	74	246.0	299	96
114.9	103	34	249.0	287	96
118.0	218	70	252.1	281	91
121.0	270	90	255.1	252	84
124.1	284	92	258.2	265	85
127.1	265	88	261.2	279	93
130.2	256	83	264.3	298	96
133.2	169	56	267.3	271	90
136.3	223	72	270.4	277	89
139.3	270	90	273.4	144	48
142.3	285	95	276.5	63	20

Diamond Drill Log

LD06-14

Date:

Logged By: DJH

Page 1/ 4

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
0.0	15.2	OB																			Overburden triconed - no core
15.2	20.6	OB																			Overburden cored boulders and clay till
20.6	24.2	SKp					5	tr				2									Ca-Garnet+Calcite Prograde Skarn massive yellow garnet PY as patches and in <vnlts loc retrograde chlorite alt'n
24.2	25.5	Md										4									Monzonite Dyke pale green/grey w/ 70% 2mm plag cnts not observed
25.5	81.4	SKp					5	tr				1		tr							Ca-Garnet+Calcite Prograde Skarn massive green/yellow ca-garnet w/ 2% lt green/grey retrograde? alt'n loc retrograde chlorite alt'n of garnet rims PY as stringers, blebs, patches w/ patches of CA and HS throughout loc patches of dk green/black retrograde chlorite alt'n loc pale red oxide? on fractures 28.2: healed breccia w/ sandy gouge 58.5: CP patch (sample 369109) loc mega garnets (30mm dia) lower cnt gradational
81.4	82.4	SKpm					5	tr				2		4						1	Mineralized Ca-Garnet+Calcite Prograde Skarn massive yellow garnet PY as xtline patches CP as patches MG as pseudos after HS lower cnt sharp, planar, S1 conformable loc patches of retrograde chlorite alt'n
82.4	86.0	MT					tr	1				1		1							Mafic Tuff?
			S1	84.7	70																grey/green chlorite phyllite w/ incipient mineralized Prograde Skarn developed loc.

Assay Sample Log LD06-14

Page: 1

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Zn
	0.0	20.6	no sample								
369080			blank				0.002	0.1	6	45	40
369081			CGS-7				0.748	3.7	10	9830	80
369082	20.6	22.9			1.3	57	0.039	0.7	617	710	32
369083	22.9	24.2			1.2	92	0.115	2.9	737	2910	55
369084	24.2	25.5			1.3	100	0.045	0.9	27	974	65
369085	25.5	26.5			1.0	100	0.060	0.5	551	653	46
369086	26.5	28.0			1.5	100	0.029	0.2	677	195	19
369087	28.0	29.6			1.6	100	0.172	0.4	1510	282	123
369088	29.6	31.1			1.5	100	0.016	0.1	1250	144	43
369089	31.1	32.6			1.5	100	0.013	0.1	1090	121	19
369090	32.6	34.1			1.5	100	0.038	0.2	865	227	28
369091	34.1	35.7			1.6	100	0.046	0.1	1560	92	29
369092	35.7	37.2			1.5	100	0.002	0.1	1120	10	13
369093	37.2	38.7			1.5	100	0.007	0.1	1010	15	17
369094	38.7	40.2			1.5	100	0.022	0.1	1140	13	28
369095	40.2	41.8			1.6	100	0.030	0.2	1130	248	23
369096	41.8	43.3			1.5	100	0.108	0.3	2140	265	39
369097	43.3	44.8			1.5	100	0.031	0.3	1260	218	20
369098	44.8	46.3			1.5	100	0.012	0.1	1640	106	22
369099	46.3	47.9			1.6	100	0.010	0.1	1330	195	20
369100			blank				0.002	0.1	1	34	38
369101			CGS-10				1.590	5.4	19	15500	82
369102	47.9	49.4			1.5	100	0.184	0.3	1660	206	114
369103	49.4	50.9			1.5	100	0.009	0.1	1660	95	58
369104	50.9	52.5			1.6	100	0.002	0.1	1590	12	48
369105	52.5	54.0			1.5	100	0.008	0.1	1480	4	19
369106	54.0	55.5			1.5	100	0.002	0.1	1430	4	43
369107	55.5	57.0			1.5	100	0.010	0.1	1130	2	20
369108	57.0	58.5			1.5	100	0.005	0.1	783	3	21
369109	58.5	60.1			1.6	100	0.009	0.1	586	77	15
369110	60.1	61.6			1.5	100	0.002	0.1	718	3	15

Assay Sample Log LD06-14

Page: 2

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Zn
369111	61.6	63.1			1.5	100	0.006	0.1	614	38	27
369112	63.1	64.6			1.5	100	0.008	0.1	451	6	14
369113	64.6	66.2			1.6	100	0.007	0.1	645	54	18
369114	66.2	67.7			1.5	100	0.002	0.1	645	5	15
369115	67.7	69.2			1.5	100	0.009	0.1	575	3	14
369116	69.2	70.7			1.5	100	0.005	0.1	874	1	10
369117	70.7	72.2			1.5	100	0.006	0.1	821	2	12
369118	72.2	73.7			1.5	100	0.091	0.1	730	2	10
369119	73.7	75.3			1.6	100	0.005	0.1	598	3	13
369120			blank				0.012	0.1	1	34	38
369121			CGS-7				0.963	3.0	9	10100	79
369122	75.3	76.8			1.5	100	0.007	0.1	710	13	11
369123	76.8	78.3			1.5	100	0.016	0.1	723	12	13
369124	78.3	79.8			1.5	100	0.008	0.1	897	11	12
369125	79.8	81.4			1.6	100	0.146	5.8	775	2990	37
369126	81.4	82.4			1.0	100	2.100	38.4	678	18400	76
369127	82.4	84.0			1.6	100	0.183	8.8	159	3420	736
369128	84.0	85.5			1.5	100	0.332	7.7	70	3830	97
369129	85.5	87.0			1.5	100	0.077	1.2	102	476	50
369130	87.0	88.4			1.4	100	0.177	1.9	57	710	51
369131	88.4	89.9			1.5	100	0.103	1.9	19	1220	44
369132	89.9	91.4			1.5	100	0.203	5.4	65	1860	64
369133	91.4	92.7			1.3	100	3.150	70.6	89	28300	605
369134	92.7	94.1			1.4	100	0.234	6.7	226	2670	75
369135	94.1	95.6			1.5	100	0.179	6.1	580	1110	92
369136	95.6	97.1			1.5	100	0.245	1.0	1250	70	14
369137	97.1	99.7			1.4	54	0.050	1.1	775	157	69
369138	99.7	101.2			1.5	100	0.023	0.1	389	14	19
369139	101.2	102.7			1.5	100	0.015	0.1	575	30	25
369140			blank				0.002	0.1	2	35	39
369141			CGS-10				1.645	5.0	19	15700	82
369142	102.7	104.2			1.5	100	0.010	0.1	516	20	15
369143	104.2	106.3			2.0	95	0.018	0.1	407	13	15

RQD Log LD06-14

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
15.2			148.4		
17.4	119	54	151.5	255	82
20.4	14	5	154.5	246	82
23.5	33	11	157.6	286	92
26.5	212	71	160.6	277	92
29.6	69	22	163.7	284	92
32.6	213	71	166.7	283	94
35.7	85	27	169.8	208	67
38.7	78	26	172.8	260	87
41.8	137	44	175.9	295	95
44.8	90	30	178.9	261	87
47.9	145	47	182.0	258	83
50.9	222	74	185.0	286	95
54.0	140	45	188.1	254	82
57.0	130	43	191.1	270	90
60.1	140	45	194.2	240	77
63.1	180	60	197.2	288	96
66.2	217	70	200.3	260	84
69.2	257	86	203.3	301	100
72.2	192	64	206.4	233	75
75.3	227	73	209.4	262	87
78.3	261	87	212.5	226	73
81.4	236	76	214.9	157	65
84.4	222	74			
87.5	176	57			
90.5	115	38		EOH @ 214.9m	
93.6	260	84			
96.6	223	74			
99.7	75	24			
102.7	231	77			
105.8	111	36			
108.8	236	79			
111.9	200	65			
114.9	134	45			
118.0	175	56			
121.0	172	57			
124.1	174	56			
127.1	224	75			
130.2	171	55			
133.2	224	75			
136.3	209	67			
139.3	216	72			
142.3	284	95			
145.4	260	84			
148.4	253	84			

Survey Log LD06-15

UTM Northing (NAD 83): 6161889.414
 UTM Easting (NAD 83): 346859.266
 Elevation (m): 1360.900
 Length (m): 328.3

Depth (ft)	Depth (m)	Azimuth	Corrected Az.	Inclination	Dip	Magnetic
0	0		64.0		-60.0	
77	23.5	41	63.0		-59.8	5752
277	84.4	41.2	63.2		-59.5	5748
1077	328.3	8.6	63.0		-59.9	8621
no surveys between 84.4 and 328.3m						

* azimuth changed (high magnetic reading)

Diamond Drill Log

LD06-15

Date:

Logged By: DJH

Page 5/6

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
190.9	252.1	SKp					5	tr					4		tr					1	Ca-Garn Prograde Skarn
																					w/ loc dark green/black CL Retrograde Skarn as selvages on PY vns
																					PY in vnlts, vns, patches
																					MG as loc patches
																					HS as xtline patches w/ PY
																					QZ as patches, vns w/ PY+HS
																					203.3-207.9: strongly fractured w/ gouge
																					217.4-218.8: strongly fractured w/ loc rubble and w/o gouge
																					loc red earthy HE in <vnlts
																					CP as loc blebs
																					231.8-233.1: strongly fractured and lost core
																					237.6-239.4: 50% patches/bands of lt greenish grey CL+CA Retrograde Skarn
																					237.2: slickensides and rubble @ 20 deg. to core axis
252.1	256.9	Md																			Monzonite Dyke
			LC	256.9	30																lt grey, non-magnetic
																					w/ 2% feldspar megacrysts to 8X10mm
																					lower cnt sharp, planar to slightly irregular
256.9	282.1	SKp					3	2				3		tr							Ca-Garn Prograde Skarn
																					grades loc to red-brown, hematite alt'd Retrograde Skarn (?)
																					PY in vns, vnlts, patches (10% loc)
																					CP as loc blebs
																					grades loc to patches of dark green/black CL and lt greyish green CL+CA
																					Retrograde Skarn
																					271.0: bleb of CP
																					258.3: 4 cms gouge
282.1	289.0	SKpm					4					1		1.5							Mineralized CPx+/-Ca-Garn Prograde Skarn
			UC	282.1	50																lt greyish green colour
			S1	282.6	55																PY in vnlts, dissems, vns
																					tr EP as loc blebs
																					CP as patches/blebs (range 0.5-3.0%)
																					loc S1 conformable bands of Ca-Garn Prograde Skarn
																					w/ relict laminated bands of mafic tuff (?) - ie incipient skarn
																					upper cnt sharp, planar
																					lower cnt gradational over 1.0 m

Assay Sample Log LD06-15

Page: 1

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Zn
	0.0	88.4	no samples								
369158	88.4	89.3			0.9	100	0.268	6.7	154	3950	100
369159	89.3	90.6			1.3	100	0.516	8.7	81	7660	72
369160			blank				0.002	0.1	1	52	38
369161			CGS-7				0.869	3.3	12	10200	80
369162	90.6	92.1			1.5	100	0.638	16.3	252	11500	61
369163	92.1	93.6			1.5	100	0.294	3.2	170	3060	37
369164	93.6	95.1			1.5	100	0.170	3.0	77	2760	34
369165	95.1	96.6			1.5	100	0.306	4.0	116	3870	22
369166	96.6	97.4			0.7	87	0.098	1.9	140	2210	30
369167	97.4	98.9			1.4	93	0.049	0.3	37	348	32
369168	98.9	99.7			0.8	100	0.085	1.0	691	951	22
369169	99.7	101.2			1.5	100	0.141	1.0	584	748	19
369170	101.2	102.7			1.5	100	0.077	1.2	325	891	18
369171	102.7	104.3			1.6	100	0.193	1.7	128	1700	25
369172	104.3	105.8			1.5	100	0.537	8.5	238	5940	32
369173	105.8	107.3			1.5	100	0.189	4.6	341	3560	20
369174	107.3	108.8			1.5	100	0.066	1.7	401	1410	20
369175	108.8	110.3			1.5	100	0.055	2.0	493	1720	20
369176	110.3	111.9			1.6	100	0.130	2.5	811	2190	15
369177	111.9	113.4			1.5	100	0.105	2.1	578	1420	235
369178	113.4	114.9			1.5	100	0.030	0.8	481	528	27
369179	114.9	116.4			1.5	100	0.130	1.0	467	809	20
369180			blank				0.002	0.2	1	36	38
369181			CGS-10				1.900	4.7	19	15600	78
369182	116.4	118.0			1.5	94	0.131	0.5	539	339	36
369183	118.0	119.5			1.5	100	0.002	0.2	609	103	12
369184	119.5	121.0			1.5	100	0.018	0.3	431	288	11
369185	121.0	122.5			1.5	100	0.015	0.6	492	455	11
369186	122.5	124.1			1.6	100	0.002	0.1	395	81	8
369187	124.1	125.6			1.5	100	0.005	0.6	654	256	8
369188	125.6	127.1			1.5	100	0.002	0.1	509	70	7

Assay Sample Log LD06-15

Page: 2

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Zn
369189	127.1	128.6			1.5	100	0.039	0.1	787	78	11
369190	128.6	130.2			1.6	100	0.002	0.1	404	61	10
369191	130.2	131.7			1.5	100	0.002	0.1	499	34	10
369192	131.7	133.2			1.5	100	0.009	0.3	705	157	11
369193	133.2	134.7			1.5	100	0.006	0.2	41	171	18
369194	134.7	135.9			1.2	100	0.008	0.4	23	229	27
	135.9	139.4	no sample								
369195	139.4	140.8			1.4	100	0.039	0.9	217	437	19
369196	140.8	142.3			1.5	100	0.022	0.2	801	320	12
369197	142.3	143.8			1.5	100	0.002	0.1	489	114	12
369198	143.8	145.4			1.6	100	0.002	0.1	419	96	13
369199	145.4	146.9			1.5	100	0.125	0.2	690	197	16
369200			blank				0.002	0.1	1	37	40
369201			CGS-7				0.977	3.3	8	9990	79
369202	146.9	148.4			1.5	100	0.049	0.1	855	196	12
369203	148.4	149.9			1.5	100	0.002	0.1	611	54	12
369204	149.9	151.5			1.6	100	0.005	0.1	583	47	13
369205	151.5	153.0			1.5	100	0.007	0.1	562	116	17
369206	153.0	154.5			1.5	100	0.012	0.1	834	101	12
369207	154.5	156.0			1.5	100	0.014	0.1	975	242	13
369208	156.0	157.6			1.6	100	0.035	0.5	907	421	14
369209	157.6	159.1			1.5	100	0.019	0.3	843	183	13
369210	159.1	160.6			1.5	100	0.044	0.4	783	344	12
369211	160.6	162.0			1.4	100	0.191	2.5	439	2200	24
	162.0	165.6	no sample								
369212	165.6	166.5			0.9	100	0.085	1.2	74	991	39
	166.5	172.2	no sample								
369213	172.2	173.7			1.5	100	0.074	1.2	708	518	263
369214	173.7	175.2			1.5	100	0.037	0.5	822	432	15
369215	175.2	176.2			1.0	100	0.076	0.9	604	613	136
369216	176.2	177.5			1.3	100	0.037	0.8	348	489	35
369217	177.5	178.9			1.4	100	0.052	0.9	690	542	23
369218	178.9	180.2			1.3	100	0.308	4.8	506	3220	129

Assay Sample Log LD06-15

Page: 3

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Zn
	180.2	190.9	no sample								
369219	190.9	192.4			1.5	100	0.002	0.4	521	245	20
369220			blank				0.008	0.1	4	37	41
369221			CGS-10				1.865	5.1	21	15400	82
369222	192.4	194.2			1.8	100	0.013	0.3	692	290	18
369223	194.2	195.7			1.5	100	0.010	0.6	862	364	40
369224	195.7	197.2			1.4	93	0.022	0.3	914	234	46
369225	197.2	198.7			1.5	100	0.002	0.2	934	121	15
369226	198.7	200.3			1.6	100	0.021	0.3	731	224	20
369227	200.3	201.8			1.5	100	0.016	0.3	683	99	19
369228	201.8	203.3			1.5	100	0.045	0.1	736	52	22
369229	203.3	204.8			1.0	67	0.015	0.1	567	199	25
369230	204.8	206.4			1.1	69	0.043	0.6	540	406	19
369231	206.4	207.9			1.2	80	0.008	0.4	825	221	15
369232	207.9	209.4			1.3	87	0.005	0.1	667	159	16
369233	209.4	210.9			1.3	87	0.020	0.6	869	441	18
369234	210.9	212.5			1.2	75	0.037	0.8	1470	618	27
369235	212.5	214.0			1.3	87	0.022	0.5	968	394	17
369236	214.0	215.5			1.2	80	0.019	0.1	722	64	12
369237	215.5	217.0			1.1	73	0.005	0.1	901	80	14
369238	217.0	218.5			1.0	67	0.005	0.1	754	39	9
369239	218.5	220.0			1.3	87	0.005	0.1	721	32	13
369240			blank				0.002	0.1	4	37	43
369241			CGS-7				1.010	3.4	13	10500	81
369242	220.0	221.6			1.1	69	0.002	0.2	447	121	17
369243	221.6	223.0			1.3	93	0.601	0.1	464	244	17
369244	223.0	224.6			1.4	88	0.006	0.3	504	95	21
369245	224.6	226.1			1.2	80	0.022	0.1	613	126	23
369246	226.1	227.7			1.2	75	0.005	0.4	718	37	18
369247	227.7	229.2			1.4	93	0.002	0.1	745	44	19
369248	229.2	230.8			1.4	87	0.009	0.1	516	61	23
369249	230.8	232.3			1.2	80	0.005	0.1	449	69	33

Assay Sample Log LD06-15

Page: 4

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Zn
369250	232.3	233.8			0.9	60	0.002	0.1	586	65	12
369251	233.8	235.3			1.1	73	0.005	0.1	538	45	14
369252	235.3	236.8			1.4	93	0.002	0.1	337	31	16
369253	236.8	238.3			1.5	100	0.021	0.2	382	186	20
369254	238.3	239.9			1.5	94	0.072	0.4	484	277	22
369255	239.9	241.4			1.5	100	0.032	0.3	1105	287	58
369256	241.4	242.9			1.5	100	0.002	0.1	555	54	16
369257	242.9	244.4			1.5	100	0.002	0.1	605	63	17
369258	244.4	246.0			1.6	100	0.002	0.2	533	50	16
369259	246.0	247.5			1.5	100	0.002	0.1	559	40	13
369260			blank				0.002	0.1	7	36	41
369261			CGS-10				1.720	5.9	20	16000	84
369262	247.5	249.0			1.3	87	0.028	0.3	966	166	15
369263	249.0	250.5			0.8	53	0.008	0.2	547	99	19
369264	250.5	252.0			0.8	53	0.006	0.1	584	69	12
	252.0	256.9	no sample								
369265	256.9	258.2			1.2	92	0.026	0.7	361	590	27
369266	258.2	259.7			1.5	100	0.021	0.6	573	403	29
369267	259.7	261.2			1.5	100	0.015	0.6	588	496	23
369268	261.2	262.7			1.5	100	0.036	0.9	447	490	31
369269	262.7	264.3			1.5	94	0.007	0.4	431	178	19
369270	264.3	265.8			1.5	100	0.064	0.3	330	76	29
369271	265.8	267.3			1.5	100	0.066	0.8	418	593	27
369272	267.3	268.8			1.5	100	0.037	1.1	338	836	31
369273	268.8	270.4			1.5	94	0.007	0.3	655	21	25
369274	270.4	271.9			1.5	100	0.020	0.4	712	384	15
369275	271.9	273.4			1.5	100	0.032	0.2	445	11	10
369276	273.4	274.9			1.4	93	0.014	0.1	682	78	12
369277	274.9	276.5			1.4	87	0.006	0.1	661	28	9
369278	276.5	278.0			1.5	100	0.002	0.1	783	17	22
369279	278.0	279.5			1.5	100	0.002	0.1	502	6	21
369280			blank				0.002	0.1	3	34	40

RQD Log LD06-15

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
11.3			145.4		
14.3	142	47	148.4	203	68
17.4	139	45	151.5	230	74
20.4	273	91	154.5	207	69
23.5	270	87	157.6	149	48
26.5	248	83	160.6	173	58
29.6	161	52	163.7	225	73
32.6	185	62	166.7	163	54
35.7	247	80	169.8	120	39
38.7	257	86	172.8	147	49
41.8	300	97	175.9	142	46
44.8	160	53	178.9	109	36
47.9	67	22	182.0	231	75
50.9	206	69	185.0	273	91
54.0	155	50	188.1	260	84
57.0	126	42	191.1	184	61
60.1	209	67	194.2	241	78
63.1	260	87	197.2	174	58
66.2	136	44	200.3	207	67
69.2	250	83	203.3	149	50
72.2	137	46	206.4	41	13
75.3	122	39	209.4	42	14
78.3	130	43	212.5	25	8
81.4	14	5	215.5	146	49
84.4	127	42	218.5	46	15
87.5	119	38	221.6	164	53
90.5	143	48	224.6	194	65
93.6	236	76	227.7	164	53
96.6	142	47	230.7	218	73
99.7	129	42	233.8	134	43
102.7	284	95	236.8	220	73
105.8	277	89	239.9	193	62
108.8	270	90	242.9	209	70
111.9	193	62	246.0	230	74
114.9	252	84	249.0	163	54
118.0	272	88	252.1	56	18
121.0	256	85	255.1	167	56
124.1	230	74	258.2	189	61
127.1	211	70	261.2	256	85
130.2	216	70	264.3	235	76
133.2	242	81	267.3	278	93
136.3	221	71	270.4	275	89
139.3	284	95	273.4	255	85
142.3	199	66	276.5	133	43
145.4	235	76	279.5	292	97

Survey Log LD06-16

UTM Northing (NAD 83): 6161868.656
 UTM Easting (NAD 83): 346771.916
 Elevation (m): 1374.937
 Length (m): 511.2

Depth (ft)	Depth (m)	Azimuth	Corrected Az.	Inclination	Dip	Magnetic
0	0		64.0		-65.0	
67	20.4	45	67.0		-64.6	5782
277	84.4	44.6	66.6		-65.0	5739
477	145.4	45.8	67.8		-65.2	5791
687	209.4	46.3	68.3		-65.3	5739
877	267.3	48.9	70.9		-65.0	5791
1067	325.2	50.1	72.1		-65.0	5791
1267	386.2	55.6	77.6		-64.5	5752
1467	447.1	60.3	82.3		-63.8	5851
1667	508.1	52.3	74.3		-63.5	5512

Diamond Drill Log

LD06-16

Date:

Logged By: DJH

Page 5/ 9

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments		
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG	
																						283.3-327.9 cont'd
			S1	306.0	21																	PY in QZ vnlt +/- MO
			S1	313.9	5																	284.2-284.5: EP+CA+Ca-Garn Prograde Skarn patch
			S1	317.2	35																	285.3-285.7: Ca-Garn+EP Prograde Skarn w/ pyrite pseudomorphs after garnet
			S1	325.7	40																	287.8-288.0: strongly fractured w/ gouge
																						288.5-288.9: strongly fractured w/ gouge
																						289.9-290.1: gouge
																						296.0-296.4: healed bxia and rubble
																						312.2: QZ+MO vnt
																						315.4: QZ+MO vnt
																						326.2-327.0: pervasive chlorite alt'n
																						327.0-327.9: metachert
327.9	331.7	SKp					4	1					2								1	Ca-Garn+CPx+CA Prograde Skarn
																						w/ loc chl+py Retrograde Skarn patches
																						PY as patches assoc. w/ Retrograde Skarn
																						MG as blebs
																						lower cnt gradational
331.7	333.1	CH					tr						2									Metachert
																						pale greenish grey, recrystallized (ie quartzite)
																						w/ minor EP+Ca-Garn Prograde Skarn patches
																						PY in <vnlt
																						lower cnt gradational
333.1	337.7	SKp					4	1					2		tr							Ca-Garn+CPx Prograde Skarn
																						w/ loc patches of CL+CA Retrograde Skarn
																						PY in vnlt, patches, blebs
																						CP as loc blebs
337.7	338.8	CH					tr						<1									Metachert
			SH	338.8	43																	as above 331.7-333.1
																						upper cnt sharp, irregular
																						lower cnt sheared w/ slicks

Diamond Drill Log

LD06-16

Date:

Logged By: DJH

Page 6/9

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
338.8	344.4	SKp					3						1	tr						3	Incipient Ca-Garn Prograde Skarn
																					w/ 30% chlorite laminae (ie mafic tuff protolith)
																					CP as loc. patches
																					MG as patches, loc 10%, increasing toward EOI
																					PY as patches, dissems.
																					lower cnt gradational
344.4	346.0	SKpm					3					3	3								Mineralized Incipient Ca-Garn Prograde Skarn
																					w/ 30% chlorite laminae (ie mafic tuff protolith)
																					as above 338.8-344.4 but mineralized w/ CP
																					PY as xtlne patches
																					CP as patches
																					345.6-346.0: massive Ca-Garn mineralized Prograde Skarn w/ sharp, irregular upper cnt
346.0	346.9	Dd										3									Diorite Dyke
			UC	346.0	37																equigranular, wkly magnetic, 10% mafics
			LC	346.9	44																wk saussurite alt'n
																					PY as dissems.
																					upper cnt sharp, planar
																					lower cnt sharp, planar
346.9	363.1	SKpm					5	tr				2	5							1	Mineralized Ca-Garn+CPx+CA Prograde Skarn
																					w/ loc patches of CL+PY Retrograde Skarn
																					loc laminations (mafic tuff protolith?)
																					CP as patches
																					PY as xtlne patches
																					MG pseudos after HS
																					loc HS patches
																					lower cnt gradational
363.1	366.7	SKp					5					1	tr							<1	Ca-Garn+CPx+CA Prograde Skarn
																					PY as dissems.
																					loc patches HS
																					MG pseudos after HS

Diamond Drill Log

LD06-16

Date:

Logged By: DJH

Page 7/9

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments		
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG	
366.7	379.0	Md									1											Monzonite Dyke
			UC	366.7	53																	non-magnetic, lt grey, 40% euhedral plag phenos to 3mm
																						5% mafics pervasively altered to chl
																						upper cnt sharp, planar
																						lower cnt gradational
379.0	412.2	SKp					5	tr				1	tr									Ca-Garn+CPx+EP+CA Prograde Skarn
																						lt green and lt reddish brown mottled colour
																						PY in xtlne patches
																						<1% EP as patches
																						loc 1% HS as xtlne patches
																						CA as xtlne patches
412.2	413.2	SKpm					3	2				4	6									Mineralized Ca-Garn+CPx+EP Prograde Skarn
																						wkly laminated (mafic tuff protolith?)
																						CP as patches/blebs
																						PY as xtlne patches
																						grades loc. to CL+CA Retrograde Skarn (30%)
																						lower cnt gradational
413.2	414.1	SKp					3	2				3										Ca-Garn+CPx+EP Prograde Skarn
																						as above 412.2 - 413.2 but w/o CP
																						lower cnt gradational
																						wkly laminated (mafic tuff protolith?)
414.1	417.3	MT										tr										Chlorite+Calcite Phyllite
			LC	417.3	52																	meta mafic tuff
																						frags of limestone
																						PY in patches near lower cnt
																						variably magnetic
																						lower cnt sharp, planar, S1 conformable
417.3	429.5	SKp					5	tr				<1										Ca-Garn+CPx+CA Prograde Skarn
			LC	429.5	52																	lt green - lt reddish brown mottled
																						418.4-418.9: grades loc to CL Retrograde Skarn w/ 2% CP as blebs
																						PY as blebs
																						lower cnt sharp, planar, S1 conformable

Diamond Drill Log

LD06-16

Date: Logged By: DJH Page 8/9

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments						
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG					
429.5	453.0	MT																								Mafic Tuff
																										w/ loc incipient Ca-Garn+CPx Prograde Skarn bands and patches
																										wkly laminated
																										dk green-grey w/ white calcite patches/frags/laminae
																										CP as specks to 432.0
																										lower cnt sharp, irregular
																										432.2-433.9: Prograde Skarn band
																										434.3-434.7: Prograde Skarn band
																										435.1-435.2: Prograde Skarn band
																										435.5-436.2: Prograde Skarn band
																										445.0-445.8: Prograde Skarn band
																										446.3-446.7: Prograde Skarn band
																										449.5-449.7: Prograde Skarn band
453.0	458.0	SKp						5	tr																	Weakly Mineralized CPx+CA+/-Ca-Garn Prograde Skarn
																										lt greyish green (CPx +CA ?) w/ lt red-brown bands and patches
																										patches (frags) of white limestone
																										CP as blebs
																										PO as blebs
458.0	461.7	LS																								Marble
																										massive, med bluish grey, recrystallized limestone
																										gouge @ lower cnt
																										upper cnt not observed
461.7	465.0	SKp																								CPx+/-Ca-Garn Prograde Skarn
																										lt greyish green w/ lt reddish brown patches and bands
																										PY as blebs
																										lower cnt gradational
465.0	496.0	MT																								Mafic Tuff
																										w/ loc incipient Prograde Skarn patches
																										as above 429.5-453.0
																										wkly laminated
																										dk green-grey w/ white calcite patches/frags/laminae
																										PY on slickensides and in Prograde Skarn bands/patches

Assay Sample Log LD06-16

Page: 1

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Zn
	0.0	261.6	no sample								
369299	261.6	263.1			1.5	100	0.031	1.2	46	1090	32
369300			blank				0.002	0.1	4	36	42
369301			CGS-10				1.750	5.2	20	15600	87
369302	263.1	264.6			1.5	100	0.014	0.5	21	470	48
369303	264.6	266.1			1.5	100	0.160	3.7	362	3280	76
369304	266.1	267.6			1.5	100	0.021	0.8	68	1130	19
369305	267.6	269.1			1.5	100	0.017	0.5	51	672	22
369306	269.1	270.5			1.3	93	0.014	0.5	49	656	18
	270.5	282.7	no sample								
369307	282.7	283.3			0.6	100	1.415	35.1	61	17100	259
369308	283.3	284.5			1.2	100	0.056	2.1	120	965	116
369309	284.5	285.7			1.2	100	0.116	1.4	234	1630	49
	285.7	326.4	no sample								
369310	326.4	327.9			1.5	100	0.024	0.8	34	546	68
369311	327.9	329.4			1.5	100	0.018	0.7	49	692	32
369312	329.4	330.9			1.5	100	0.024	0.7	81	778	44
369313	330.9	331.7			0.8	100	0.013	0.6	110	426	48
369314	331.7	333.1			1.4	100	0.009	0.4	10	378	24
369315	333.1	334.4			1.3	100	0.032	0.5	47	628	34
369316	334.4	335.9			1.5	100	0.030	0.9	79	1310	27
369317	335.9	337.7			1.8	100	0.036	0.5	73	887	25
369318	337.7	338.8			1.1	100	0.010	0.2	11	91	33
369319	338.8	340.5			1.7	100	0.016	0.8	74	729	44
369320			blank				0.002	0.1	6	36	40
369321			CGS-7				1.025	3.4	13	9900	85
369322	340.5	342.0			1.5	100	0.056	1.2	82	1190	34
369323	342.0	343.5			1.5	100	0.059	1.2	68	1350	37
369324	343.5	344.4			0.9	100	0.132	2.8	54	2830	63
369325	344.4	346.0			1.6	100	0.739	11.0	61	11600	154
369326	346.0	346.9			0.9	100	0.093	2.3	5	3110	28
369327	346.9	348.1			1.2	100	1.485	37.0	90	41400	316

Assay Sample Log LD06-16

Page: 2

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Zn
369328	348.1	349.6			1.5	100	0.795	15.1	80	26200	267
369329	349.6	351.1			1.5	100	0.090	1.3	74	2760	76
369330	351.1	352.7			1.6	100	0.743	8.7	63	18500	124
369331	352.7	354.2			1.5	100	1.010	12.9	74	32400	264
369332	352.7	354.2	duplicate				1.720	12.0	65	31900	237
369333	354.2	355.7			1.5	100	2.020	16.2	77	36900	269
369334	355.7	357.2			1.5	100	1.165	16.7	209	33100	193
369335	357.2	358.8			1.6	100	0.415	7.0	108	10500	106
369336	358.8	360.3			1.5	100	1.125	16.6	75	26400	123
369337	360.3	361.8			1.5	100	0.900	19.5	77	20200	99
369338	361.8	363.1			1.3	100	0.590	12.4	84	9820	59
369339	363.1	364.9			1.8	100	0.032	0.4	73	261	26
369340			blank				0.002	0.1	4	38	40
369341			CGS-10				1.770	4.7	19	15700	83
369342	364.9	366.7			1.8	100	0.028	0.5	183	326	35
	366.7	379.0	no sample								
369343	379.0	380.1			1.1	100	0.024	0.1	133	113	15
369344	380.1	381.6			1.5	100	0.046	0.2	109	113	18
369345	381.6	383.1			1.5	100	0.028	1.0	90	450	20
369346	383.1	384.6			1.5	100	0.089	2.3	112	797	34
369347	384.6	386.2			1.6	100	0.142	4.1	66	1710	35
369348	386.2	387.7			1.5	100	0.017	0.1	78	78	20
369349	387.7	389.2			1.5	100	0.006	0.3	114	33	14
369350	389.2	390.7			1.5	100	0.024	0.4	68	238	26
369351	390.7	392.3			1.6	100	0.138	3.5	86	1180	39
369352	392.3	393.8			1.5	100	0.116	0.6	120	365	16
369353	393.8	395.3			1.5	100	0.088	0.2	84	171	24
369354	395.3	396.8			1.5	100	0.047	1.1	46	385	44
369355	396.8	398.4			1.6	100	0.023	0.2	86	79	73
369356	398.4	399.9			1.5	100	0.014	0.1	97	25	15
369357	399.9	401.4			1.5	100	0.006	0.1	127	22	12
369358	401.4	402.9			1.5	100	0.089	2.5	114	722	32
369359	402.9	404.5			1.6	100	0.113	2.6	69	750	62

Assay Sample Log LD06-16

Page: 3

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Zn
369360			blank				0.002	0.1	1	35	39
369361			CGS-7				0.868	3.4	10	10300	82
369362	404.5	406.0			1.5	100	0.017	0.1	54	53	25
369363	406.0	407.5			1.5	100	0.076	0.1	69	10	14
369364	407.5	409.0			1.5	100	0.022	0.1	83	8	27
369365	409.0	410.6			1.6	100	0.040	0.1	102	18	19
369366	410.6	412.2			1.6	100	0.225	0.1	92	47	11
369367	412.2	413.2			1.0	100	2.240	59.6	57	19400	309
369368	413.2	414.1			0.9	100	0.080	2.0	55	642	45
	414.1	417.3	no sample								
369369	417.3	418.9			1.6	100	0.528	11.5	49	4320	60
369370	418.9	420.4			1.5	100	0.022	0.2	53	69	21
369371	420.4	421.9			1.5	100	0.036	0.1	49	116	19
369372	421.9	423.4			1.5	100	0.153	3.6	36	1630	78
369373	423.4	424.9			1.5	100	0.048	1.5	30	607	34
369374	424.9	426.4			1.5	100	0.057	1.1	51	404	24
369375	426.4	427.9			1.5	100	0.060	1.0	55	370	30
369376	427.9	429.5			1.6	100	0.102	1.9	60	714	40
369377	429.5	431.0			1.5	100	0.099	2.4	38	928	182
369378	431.0	432.5			1.5	100	0.067	1.3	45	555	72
	432.5	453.0	no sample								
369379	453.0	454.5			1.5	100	0.446	6.4	38	2690	62
369380			blank				0.002	0.1	4	37	40
369381			CGS-10				1.810	5.2	20	15000	85
369382	454.5	456.0			1.5	100	0.155	2.1	45	902	36
369383	456.0	457.0			1.0	100	0.233	3.6	34	1460	50
369384	457.0	458.0			1.0	100	0.126	2.3	36	1370	49
	458.0	511.0	no sample								
EOH @ 511.0 m											
	344.4	363.1	18.7m				0.873	13.5	85	21238	162

RQD Log LD06-16

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
6.1			139.3		
8.2	0	0	142.3	174	58
11.3	20	6	145.4	245	79
14.3	231	77	148.4	182	61
17.4	224	72	151.5	222	72
20.4	117	39	154.5	194	65
23.5	63	20	157.6	220	71
26.5	103	34	160.6	135	45
29.6	85	27	163.7	144	46
32.6	41	14	166.7	183	61
35.7	154	50	169.8	96	31
38.7	146	49	172.8	222	74
41.8	62	20	175.9	173	56
44.8	139	46	178.9	208	69
47.9	162	52	182.0	290	94
50.9	132	44	185.0	208	69
54.0	132	43	188.1	200	65
57.0	186	62	191.1	74	25
60.1	173	56	194.2	101	33
63.1	230	77	197.2	213	71
66.2	173	56	200.3	239	77
69.2	194	65	203.3	90	30
72.2	259	86	206.4	65	21
75.3	120	39	209.4	137	46
78.3	252	84	212.5	207	67
81.4	282	91	215.5	232	77
84.4	268	89	218.5	180	60
87.5	220	71	221.6	110	35
90.5	233	78	224.6	123	41
93.6	243	78	227.7	119	38
96.6	205	68	230.7	282	94
99.7	246	79	233.8	289	93
102.7	233	78	236.8	307	102
105.8	103	33	239.9	294	95
108.8	122	41	242.9	296	99
111.9	217	70	246.0	247	80
114.9	192	64	249.0	244	81
118.0	225	73	252.1	241	78
121.0	236	79	255.1	283	94
124.1	194	63	258.2	292	94
127.1	127	42	261.2	261	87
130.2	150	48	264.3	238	77
133.2	78	26	267.3	285	95
136.3	214	69	270.4	174	56
139.3	255	85	273.4	240	80

RQD Log LD06-16

Date: Page: 2

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
273.4			407.5		
276.5	284	92	410.6	269	87
279.5	231	77	413.6	268	89
282.6	231	75	416.7	210	68
285.6	178	59	419.7	245	82
288.7	31	10	422.8	212	68
291.7	180	60	425.8	248	83
294.7	298	99	428.9	232	75
297.8	48	15	431.9	288	96
300.8	256	85	435.0	247	80
303.9	277	89	438.0	236	79
306.9	236	79	441.1	231	75
310.0	200	65	444.1	179	60
313.0	285	95	447.2	204	66
316.1	242	78	450.2	250	83
319.1	228	76	453.2	240	80
322.2	292	94	456.3	275	89
325.2	226	75	459.3	228	76
328.3	205	66	462.4	217	70
331.3	259	86	465.4	165	55
334.4	265	85	468.5	182	59
337.4	288	96	471.5	112	37
340.5	262	85	474.6	129	42
343.5	265	88	477.6	180	60
346.6	228	74	480.7	190	61
349.6	276	92	483.7	186	62
352.7	282	91	486.8	213	69
355.7	296	99	489.8	260	87
358.8	260	84	492.9	267	86
361.8	296	99	495.9	188	63
364.9	280	90	499.0	198	64
367.9	212	71	502.0	290	97
370.9	291	97	505.1	282	91
374.0	280	90	508.1	270	90
377.0	220	73	511.2	230	74
380.1	240	77			
383.1	282	94		EOH @ 511.2m	
386.2	282	91			
389.2	231	77			
392.3	289	93			
395.3	264	88			
398.4	264	85			
401.4	271	90			
404.5	281	91			
407.5	268	89			

Survey Log LD06-17

UTM Northing (NAD 83): 6161868.656
UTM Easting (NAD 83): 346771.916
Elevation (m): 1374.937
Length (m): 538.6

Depth (ft)	Depth (m)	Azimuth	Corrected Az.	Inclination	Dip	Magnetic
0	0		64.0		-75.0	
207	63.1	45.5	67.5		-76.0	5746
407	124.0	46.6	68.6		-76.1	5737
617	188.1	48.5	70.5		-75.9	5752
817	249.0	50	72.0		-76.0	5755
1017	310.0	52.6	74.6		-76.0	5751
1207	367.9	56.6	78.6		-75.6	5716
1407	428.8	57.4	79.4		-74.8	5806
1597	486.7	59.6	81.6		-75.2	5700
1767	538.6	58.5	80.5		-74.4	5750

Diamond Drill Log

LD06-17

Date:

Logged By: DJH

Page 1/12

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
0.0	9.1	OB																			Overburden triconed - no core
9.1	13.7	SPbh				5				tr	tr		2								Biotite Hornfelses Siliceous Phyllite loc. ser+chl alt'n of biotite rich laminae PY in vnlt's, <vnlt's lower cnt not observed
13.7	14.6	Dd											2								Diorite Dyke v. weakly mag., equigranular, 5% mafics lower cnt gradational PY as dissems.
14.6	17.6	SKp					5						6								Ca-Garnet+Epidote+Calcite Prograde Skarn PY as xtlne patches, vnlt's
17.6	28.4	Dd											2								Diorite Dyke as above 13.7-14.6 upper cnt gradational lower cnt not observed
28.4	29.8	MT											2								Chlorite+Calcite Phyllite mafic tuff med to dk gy-green numerous calcite vns, vnlt's, stringers wkly to mod'ly phyllitic PY as patches 29.0-29.2: broken core and gouge lower cnt notobserved
29.8	32.1	Dd					tr						2								Diorite Dyke as above 13.7-14.6 wk EP alt'n as blebs PY as dissems. and as xtlne patches in skarn grades loc. to Ca-Garnet+Epidote+Calcite Endoskarn lower cnt not observed

Diamond Drill Log

LD06-17

Date:

Logged By: DJH

Page 2/ 12

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments		
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG	
32.1	33.6	MT					1															Chlorite+Calcite Phyllite dk greenish grey, wkly laminated w/ 20% skarn patches lower cnt gradational mafic tuff?
33.6	35.0	SKp				4	1					2										Ca-Garnet+Epidote+Calcite Prograde Skarn grades loc.to patches of CL+EP+MG retrograde skarn PY in vnlt's, stringers lower cnt gradational
35.0	35.8	Dd					tr					2										Diorite Dyke w/ incipient endoskarn alt'n tr EP alt'n as blebs PY in <vnlt's, vnlt's, stringers lower cnt gradational
35.8	37.8	SKp					5					2										Ca-Garnet+CPx+EP Prograde Skarn PY as patches, vnlt's, dissems lower cnt gradational
37.8	39.5	Dd										2										Diorite Dyke PY in <vnlt's, vnlt's
39.5	41.2	SKp					4	1				5								2		Ca-Garn+CPx+EP+CA Prograde Endoskarn <10% CL+CA retrograde alt'n PY as xtlne patches MG as loc. patches lower cnt gradational
41.2	42.8	SKr					1	4				10								3		CL+CA+MG Retrograde Skarn w/ <10% Ca-Garn+CPx prograde skarn PY as xtlne patches MG as loc. patches lower cnt gradational (ie endoskarn)

Diamond Drill Log

LD06-17

Date:

Logged By: DJH

Page 3/12

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
42.8	45.5	Dd										2									Diorite Dyke loc. EP at'l'n patches PY in vnlts, <vnlts lower cnt gradational
45.5	47.3	Dd					2					2									Diorite Dyke w/ incipient Ca-Garn+CPx+CA prograde skarn ie gradational contact zone
47.3	56.3	SKp					4	1				10	tr						1		Ca-Garn+EP+CPx+CA Prograde Endoskarn grades loc. to Diorite Dyke PY as xtlne patches MG as loc. patches EP as loc. patches CP as blebs at 55.5 minor patches of CL retrograde alteration lower cnt gradational
56.3	79.0	Dd								1		2									Diorite Dyke equigranular, med to fine grained, wkly magnetic, 10% mafics pervasive CL alt'n of mafics med greenish grey PY in QZ vn, vnlts, <vnlts,dissems. lower cnt gradational
79.0	121.2	Md										4									Monzonite Dyke lt grey w/ 3% mafics occasional feldspar phenos to 8X10mm non-magnetic med grained PY as dissems., <vnlts lower cnt gradational
121.2	144.8	Dd								1		<1									Diorite Dyke as above 56.3-79.0 PY in <vnlts, vnlts, vns

Diamond Drill Log

LD06-17

Date:

Logged By: DJH

Page 4/12

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
																					121.2-144.8 cont'd
																					136.2: QZ+PY+MO vn @ 35/10mm
																					136.3-136.5: Biotite Hornfelsed Siliceous Phyllite fragment
144.8	165.4	Md										1									Monzonite Dyke
																					as above 79.0-121.2
																					monzonite appears to have a chilled margin against diorite
																					5% feldspar megacrysts to 6X8mm
																					PY as dissems.
																					tr MO in QZ vnlt
																					lower cnt gradational
165.4	194.2	Dd										1									Diorite Dyke
																					as above 56.3-79.0
																					magnetic, equigranular (1-2mm), 10% mafics
																					PY in vnlt, <vnlt, rare vns w/ QZ
																					tr MO in QZ vns
																					lower cnt not observed
																					178.4: PY+QZ vn @ 30/30mm
																					190.1-190.5: strongly fractured w/ gouge
																					191.0-191.8: strongly fractured w/o gouge
194.2	205.8	SPbh				5			1	1		1									Biotite Hornfelsed Siliceous Phyllite
			S1	198.0	43																loc ser+chl alt'n of biotite rich laminae
			S1	204.2	34																PY as blebs, vnlt, <vnlt
205.8	210.6	Dd										1									Diorite Dyke
																					as above 56.3-79.0
																					magnetic, equigranular (1-2mm), 10% mafics
																					upper cnt gradational
																					lower cnt sharp, irregular, w/o chilled margin
																					PY in vnlt, <vnlt, dissems.
210.6	220.6	Md									1										Monzonite Dyke
																					pale greenish grey, non-magnetic,
																					2% feldspar megacrysts

Diamond Drill Log

LD06-17

Date:

Logged By: DJH

Page 6/12

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
																					261.4-291.0 cont'd
																					loc ser. alt'n selvages on <vnlt
																					rare QZ+PY+MO+CA vns
																					286.3: Biotite Hornfelses Siliceous Phyllite fragment
																					290.2-291.0: strongly fractured w/ gouge and slickensides
291.0	292.2	Md										2									Monzonite Dyke
																					lt grey, non-magnetic, med grained (2-4mm), <2% feldspar megacrysts to 4X8mm
																					upper cnt sheared?
																					lower cnt gradational
																					PY as dissems., vns
292.2	294.6	Dd										3									Diorite Dyke
																					med grey, equigranular, v. wkly magnetic
																					PY as dissems., <vnlt
																					lower cnt gradational
294.6	304.3	SPbh					5					1									Biotite Hornfelses Siliceous Phyllite
			S1	297.7	45																PY as dissems, <vnlt
			S1	303.4	30																
304.3	305.9	SKp					1	4	tr			7								3	Ca-Garn Prograde Skarnoid
																					w/ loc. patches of dk green chlorite retrograde alt'n
																					grades loc to Biotite Hornfelses Siliceous Phyllite
																					PY as xtlne patches
																					MG as patches
305.9	307.4	SKp					2	3			tr	5									Incipient Ca-Garn Prograde Skarnoid
																					grades loc. laminated Biotite Hornfelses Siliceous Phyllite
																					PY in vnlt, <vnlt (w/ chl alt'n selvages)
																					306.9: QZ+MO vnlt
307.4	357.5	SPbh					5	tr			1	1	<1								Biotite Hornfelses Siliceous Phyllite
			S1	309.3	25																w/ minor patches/bands of Prograde Skarn
			S1	314.5	20																PY in vnlt, dissems.
			S1	321.3	15																312.4-312.6: strongly fractured w/ gouge

Diamond Drill Log

LD06-17

Date:

Logged By: DJH

Page 7/ 12

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
																					307.4-357.5 cont'd
			S1	326.7	30																317.6-318.4: strongly fractured w/ gouge
			S1	331.6	30																317.0-320.0: skarnoid bands
			S1	337.0	44																327.9-328.1: incipient skarnoid band
			S1	341.0	32																332.5-333.5: strongly fractured w/ gouge
			S1	348.1	35																333.6: 4 SL (yellow)+CA vns
			S1	353.6	40																biotite altered to ser+chl locally
																					355.0: 5cm dyklet - strongly fractured w/ slicks
357.5	359.0	Dd											3								Diorite Dyke (?)
			UC	357.5	25																dark grey/green, non-magnetic , wkly porphyritic
			LC	359.0	50																w/ rare feldspar megacrysts to 6X10mm
																					PY in vnlt, patches, dissems
																					inclusions of Biotite Hornfelses Siliceous Phyllite
																					* not completely equigranular like typical Diorite Dyke
																					upper cnt sharp, planar
																					lower cnt sharp, planar, x-cuts S1
359.0	371.3	SPbh					5	tr					<1								Biotite Hornfelses Siliceous Phyllite
			S1	361.0	35																PY as <vnlt, dissems.
			S1	365.3	57																loc QZ+MO vnlt
			S1	369.4	20																365.5-366.2: incipient Prograde Skarnoid w/ relict laminae; PY+MG
371.3	384.8	SKp					5	tr					7	tr							Ca-Garn+CPx+CA Prograde Skarn
																					w/ <5% dk green chlorite rich Retrograde Skarn
																					PY in xtline patches, vnlt
																					CP as loc. patches
																					MG as patches
																					upper cnt sharp, irregular
																					lower cnt gradational over 1.0m (ie Retrograde Skarn increasing)
																					rare QZ+MO+PY vns
																					384.0: vn w/ CP+MO+CA
384.8	386.9	SKrm				tr	1	4					10	0.3							Wkly Mineralized CL+MG+PY Retrograde Skarn
																					grades loc to Ca-Garn+CPx Prograde Skarn
																					MG as patches to 20cms
																					PY as xtline patches

Diamond Drill Log

LD06-17

Date: Logged By: DJH Page 8/ 12

From	To	Rock	Struct	@	CA	Alteration								Mineralization							Comments
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN	MG	
																					384.8-386.9 cont'd
																					CP as isolated blebs (hard to estimate grade)
																					lower cnt gradational
																					385.8-386.2: grades loc to Biotite Hornfelsed Siliceous Phyllite
386.9	388.7	SPp					4	1					7								Ca-Garn+CPx+CA Prograde Skarn
																					PY as xtlne patches
																					MG as patches
																					387.7-387.8: monzonite dyklet
																					388.2-388.6: monzonite dyklet
																					lower cnt gradational
388.7	414.1	SPbh					5	tr					1								Biotite Hornfelsed Siliceous Phyllite
			S1	390.5	40																w/ minor skarn patches/bands at upper contact (gradational)
			S1	395.1	35																PY as blebs, <vnlts, vnlts
			S1	401.4	42																loc ser alt'n of biotite
			S1	407.0	45																loc vns w/ QZ+PY+MO+CP
			S1	412.5	35																402.4-402.5: strongly fractured w/ gouge
																					403.0-404.1: dark greenish grey, fine grained dyke w/ loc endoskarn alt'n
																					408.1-408.8: Prograde Skarn band w/ loc Retrograde Skarn patches; QZ+MO+CP vn
414.1	417.7	Md											1								Monzonite Dyke
			UC	414.1	25																PY as dissems.
			LC	417.7	15																wkly megacrystic w/ 2% feldspar phenos to 8X10mm
																					upper cnt sharp, planar
																					lower cnt sharp, planar
417.7	422.2	SPbh					5						<1		tr						Biotite Hornfelsed Siliceous Phyllite
																					PY in vnlts, dissems
																					420.0-420.3: Monzonite Dyke w/ sharp cnts
																					421.9-422.2: 0.5% CP
422.2	424.0	SKpm					5	tr					2		5						Mineralized Ca-Garn+CPx+CA Prograde Skarn
																					w/ loc patches of dark green Chl Retrograde Skarn
																					PY in vnlts, patches
																					CP interstitial to garnet grains, loc patches/blebs

Diamond Drill Log

LD06-17

Date:

Logged By: DJH

Page 9/12

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments		
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG	
424.0	425.4	SKp					3	2					1		0.5							Ca-Garn+CPx+CA Prograde Skarn
																						w/ 30% CL Retrograde Skarn
																						PY as blebs
																						CP as loc. blebs
425.4	426.4	Md																				Monzonite Dyke
			UC	425.4	50																	no mineralization
			LC	426.4	63																	no alteration
																						upper cnt sharp, planar
																						lower cnt sharp, planar
426.4	430.4	SKpm					5	tr					1		1.5						1	Mineralized Ca-Garn+CPx+CA Prograde Skarn
																						lt green/lt red-brown patchy coloration
																						CP is not distributed evenly (range 0.5 to 2%)
																						CP interstitial to garnet grains; loc. patches
																						loc. QZ+MO vns/vnlts
																						loc patches of chlorite Retrograde Skarn alt'n
																						MG as loc. patches
																						PY as blebs, patches
																						lower cnt gradational
430.4	438.3	SKp					5	tr					1		tr						0.5	Ca-Garn+CPx+CA Prograde Skarn
																						as above 426.4-430.4 but w/o significant CP mineralization
																						PY as blebs, patches, vnlts
																						HS as loc patches
																						MG as loc pseudomorphs after HS
																						retrograde CL alt'n selvages on PY vnlts
																						MO loc in QZ vns
																						lower cnt gradational
438.3	440.8	SKpm					5	tr					1		5						0.5	Mineralized Ca-Garn+CPx+CA Prograde Skarn
																						as above 422.2-424.0
																						CP interstitial to garnet grains
																						MG as loc patches
																						HS as loc patches
																						PY as loc patches

Diamond Drill Log

LD06-17

Date:

Logged By: DJH

Page 10/ 12

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
																					438.3-440.8 cont'd
																					lower cnt gradational
																					CL Retrograde Skarn alt'n patches
440.8	453.9	SKp					5	tr					2		0.5						Ca-Garn+CPx+CA Prograde Skarn
																					w/ bands of mineralized Prograde Skarn (5% CP)
																					MG as loc patches
																					PY as xtlne patches
																					loc patches of HS+EP+PY
																					448.7-449.1: mineralized Prograde Skarn w/ 5% CP
																					451.7-452.0: mineralized Prograde Skarn w/ 5% CP
																					loc patches/bands w/ CL Retrograde Skarn alt'n
453.9	457.7	SKpm					5	tr					1		6						Mineralized Ca-Garn+CPx+CA Prograde Skarn
																					w/ loc. Retrograde Skarn patches and bands
																					CP as patches and interstitial to garnet grains
																					PY as patches
																					0.5% HS as patches
																					MG as patches
																					456.3-457.0: HE rich patches/bands
																					457.2-457.7: CP decreasing
457.7	464.8	Md						tr					1								Monzonite Dyke
			UC	457.7	60																typical lt grey monzonite w/ 10% mafics; non-magnetic; fine to med grained
																					mafics altered to chlorite
																					occasional feldspar megacrysts to 8X10mm
																					upper cnt sharp, planar
																					lower cnt gradational
																					PY as dissems.
464.8	494.2	SKp					5	tr					2		tr						Ca-Garn+CPx+CA Prograde Skarn
			S1	478.5	49																PY as patches
																					CP as specks
																					MG as patches
																					0.5% HS as patches
																					loc red HE on fractures

Diamond Drill Log

LD06-17

Date:

Logged By: DJH

Page 11/ 12

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments		
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG	
																						464.8-494.2 cont'd
																						loc wk laminations (mafic tuff or Biotite Hornfelsed Siliceous Phyllite protolith)
																						468.6: QZ vn @ 35/20mm
494.2	498.0	Md																				Monzonite Dyke
			UC	494.2	65																	v. pale grey variety (alt'd)
			LC	498.0	60																	30% euhedral feldspar to 4mm in an aphanitic matrix
																						no mafics
																						upper cnt sharp, planar, gouge
																						lower cnt sharp, planar, minor gouge
																						494.2-495.2: strongly fractured w/ loc gouge
498.0	499.5	SKp					5	tr					<1		tr						10	Ca-Garn+CPx+CA Prograde Skarn
																						CP as loc blebs
																						PY as patches
																						MG as large patches (replacing calc-silicate minerals?)
																						loc CL Retrograde Skarn alt'n
499.5	535.1	SKp					5	tr					1		tr						0.5	Ca-Garn+CPx+CA Prograde Skarn
			S1	500.2	40																	CP as loc blebs
																						MG as loc patches
																						PY as patches/blebs
																						patches and bands of CL Retrograde Skarn alt'n
																						loc wk laminations as above 464.8-494.2
																						HS as loc patches
			FLT	516.8	42																	504.8-505.0: magnetite rich skarn
																						513.5-513.7: Retrograde Skarn w/ red/earthy HE
																						516.0-516.8: strongly fractured w/ loc gouge
																						522.6-528.0: loc. hematite alt'n
																						529.5-529.7: strongly fractured w/ gouge
																						lower cnt gradational
535.1	537.0	SPbh					5	tr					tr									Biotite Hornfelsed Siliceous Phyllite
																						PY as dissems.
																						lower cnt gradational

Assay Sample Log LD06-17

Page: 1

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Zn
	0.0	14.6	no sample								
369385	14.6	17.6			2.9	97	0.120	2.8	44	1640	29
	17.6	39.5	no sample								
369386	39.5	41.0			1.5	100	0.027	0.8	30	1900	44
369387	41.0	42.8			1.7	94	0.035	1.5	39	3100	47
	42.8	45.5	no sample								
369388	45.5	47.0			1.5	100	0.026	1.2	40	1790	34
369389	47.0	48.5			1.5	100	0.013	0.5	64	982	25
369390	48.5	50.0			1.4	93	0.025	0.5	52	617	29
369391	50.0	51.5			1.4	93	0.018	0.7	14	1100	28
369392	51.5	53.0			1.4	93	0.037	1.8	33	1630	34
369393	53.0	54.5			1.5	100	0.036	0.9	45	705	56
369394	54.5	56.0			1.5	100	0.097	3.0	71	3010	56
369395	56.0	57.0			1.0	100	0.024	0.4	67	698	33
	57.0	304.3	no sample								
369396	304.3	305.9			1.6	100	0.050	1.2	80	2040	24
369397	305.9	307.4			1.5	100	0.014	0.6	51	850	44
	307.4	371.3	no sample								
369398	371.3	372.4			1.1	100	0.026	0.7	68	737	24
369399	372.4	374.0			1.6	100	0.033	1.3	91	2020	19
369400			blank				0.002	0.2	9	37	36
369401			CGS-7				0.934	3.0	7	9740	85
369402	374.0	375.5			1.5	100	0.048	1.9	56	2350	21
369403	375.5	377.0			1.5	100	0.015	0.7	67	894	16
369404	377.0	378.5			1.5	100	0.008	0.5	54	695	18
369405	378.5	380.1			1.6	100	0.006	0.4	32	284	19
369406	380.1	381.6			1.5	100	0.006	0.2	47	89	23
369407	381.6	383.1			1.5	100	0.013	1.1	133	487	46
369408	383.1	384.8			1.7	100	0.050	2.5	99	2520	30
369409	384.8	385.8			1.0	100	0.076	3.8	92	4500	36
369410	385.8	386.9			1.1	100	0.050	2.4	102	1470	46
369411	386.9	388.2			1.3	100	0.009	0.5	49	380	24

Assay Sample Log LD06-17

Page: 2

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Zn
	388.2	422.2	no sample								
369412	422.2	424.0			1.8	100	1.385	24.4	38	31300	150
369413	424.0	425.4			1.4	100	0.096	3.0	33	3250	72
369414	425.4	426.4			1.0	100	0.017	1.4	12	1240	36
369415	426.4	427.9			1.5	100	0.117	3.7	22	3760	55
369416	427.9	429.4			1.5	100	0.409	6.9	38	8300	85
369417	429.4	430.9			1.5	100	0.395	6.0	36	8760	76
369418	430.9	432.4			1.5	100	0.063	1.6	24	2250	55
369419	432.4	433.9			1.5	100	0.088	1.7	25	2320	42
369420			blank				0.005	0.1	3	45	38
369421			CGS-10				1.815	6.1	13	15600	89
369422	433.9	435.4			1.5	100	0.074	1.3	34	1580	28
369423	435.4	436.9			1.5	100	0.043	1.0	36	1460	26
369424	436.9	438.3			1.4	100	0.123	1.6	42	2260	28
369425	438.3	440.8			2.4	96	0.881	11.4	36	14300	86
369426	440.8	442.3			1.5	100	0.035	0.8	46	1110	38
369427	442.3	443.8			1.5	100	0.079	0.8	36	1230	38
369428	443.8	445.3			1.5	100	0.061	0.9	46	1080	37
369429	445.3	446.8			1.5	100	0.213	1.6	26	2090	43
369430	446.8	448.3			1.5	100	0.027	0.7	21	660	44
369431	448.3	449.8			1.5	100	0.787	16.3	33	13300	72
369432	449.8	451.3			1.5	100	0.009	0.1	33	139	23
369433	451.3	452.8			1.5	100	0.243	3.8	35	2510	44
369434	452.8	453.9			1.1	100	0.008	0.2	47	120	20
369435	453.9	455.4			1.5	100	4.520	48.8	57	40000	470
399436	453.9	455.4	duplicate				2.490	46.9	51	37600	434
369437	455.4	456.9			1.5	100	3.580	41.7	64	32900	315
369438	456.9	457.7			0.8	100	0.870	18.2	67	16700	291
	457.7	464.8	no sample								
369439	464.8	466.3			1.5	100	0.017	0.3	45	208	22
369440			blank				0.006	0.1	9	41	37
369441			CGS-7				0.922	3.3	11	9850	79
369442	466.3	467.8			1.5	100	0.014	0.4	70	270	26

Assay Sample Log LD06-17

Page: 3

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Zn
369443	467.8	469.3			1.5	100	0.005	0.1	96	28	17
369444	469.3	470.8			1.5	100	0.010	0.2	72	64	32
369445	470.8	472.3			1.5	100	0.007	0.1	82	17	18
369446	472.3	473.8			1.5	100	0.006	0.1	111	15	14
369447	473.8	475.3			1.5	100	0.006	0.1	119	17	16
369448	475.3	476.8			1.5	100	0.009	0.1	135	11	12
369449	476.8	478.3			1.5	100	0.012	0.2	119	17	16
369450	478.3	479.8			1.5	100	0.002	0.1	84	10	25
369451	479.8	481.3			1.5	100	0.002	0.2	65	11	19
369452	481.3	482.8			1.5	100	0.002	0.1	51	6	16
369453	482.8	484.3			1.5	100	0.005	0.1	76	10	17
369454	484.3	485.8			1.5	100	0.002	0.1	71	7	14
369455	485.8	487.3			1.5	100	0.002	0.1	53	7	16
369456	487.3	488.8			1.5	100	0.005	0.1	21	9	24
369457	488.8	490.3			1.5	100	0.008	0.1	45	29	24
369458	490.3	491.8			1.5	100	0.006	0.1	64	8	16
369459	491.8	493.3			1.5	100	0.017	0.1	66	15	20
369460			blank				0.002	0.1	1	35	38
369461			CGS-10				1.935	5.1	20	15600	80
369462	493.3	494.2			0.9	100	0.013	0.2	86	17	20
	494.2	498.0	no sample								
369463	498.0	499.5			1.5	100	0.048	1.2	45	933	39
369464	499.5	500.5			1.0	100	0.007	0.1	81	23	30
369465	500.5	502.0			1.5	100	0.011	0.3	60	223	28
369466	502.0	503.5			1.5	100	0.006	0.2	56	184	29
369467	503.5	505.1			1.6	100	0.002	0.1	62	12	25
369468	505.1	506.6			1.5	100	0.002	0.1	43	9	25
369469	506.6	508.1			1.5	100	0.002	0.1	50	4	27
369470	508.1	509.6			1.5	100	0.002	0.1	34	10	31
369471	509.6	511.2			1.6	100	0.002	0.1	46	9	24
369472	511.2	512.7			1.5	100	0.005	0.1	48	8	33
369473	512.7	514.2			1.5	100	0.002	0.1	65	6	29
369474	514.2	515.7			1.5	100	0.012	0.1	60	6	20

RQD Log LD06-17

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
9.1			142.3		
11.3	10	5	145.4	170	55
14.3	112	37	148.4	220	73
17.4	230	74	151.5	250	81
20.4	214	71	154.5	260	87
23.5	130	42	157.6	261	84
26.5	98	33	160.6	211	70
29.6	63	20	163.7	197	64
32.6	104	35	166.7	121	40
35.7	134	43	169.8	133	43
38.7	214	71	172.8	250	83
41.8	147	47	175.9	240	77
44.8	172	57	178.9	215	72
47.9	200	65	182.0	250	81
50.9	111	37	185.0	100	33
54.0	141	45	188.1	193	62
57.0	168	56	191.1	126	42
60.1	147	47	194.2	45	15
63.1	204	68	197.2	171	57
66.2	166	54	200.3	245	79
69.2	204	68	203.3	197	66
72.2	177	59	206.4	118	38
75.3	140	45	209.4	222	74
78.3	145	48	212.5	184	59
81.4	188	61	215.5	284	95
84.4	255	85	218.5	157	52
87.5	230	74	221.6	188	61
90.5	247	82	224.6	179	60
93.6	290	94	227.7	90	29
96.6	283	94	230.7	241	80
99.7	270	87	233.8	231	75
102.7	186	62	236.8	227	76
105.8	200	65	239.9	232	75
108.8	180	60	242.9	214	71
111.9	288	93	246.0	289	93
114.9	250	83	249.0	244	81
118.0	246	79	252.1	215	69
121.0	196	65	255.1	284	95
124.1	205	66	258.2	277	89
127.1	130	43	261.2	269	90
130.2	220	71	264.3	229	74
133.2	202	67	267.3	160	53
136.3	210	68	270.4	247	80
139.3	250	83	273.4	164	55
142.3	177	59	276.5	234	75

RQD Log LD06-17

Date: Page: 2

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
276.5			410.6		
279.5	200	67	413.6	228	76
282.6	217	70	416.7	213	69
285.6	234	78	419.7	247	82
288.7	260	84	422.8	180	58
291.7	142	47	425.8	290	97
294.7	192	64	428.9	273	88
297.8	147	47	431.9	273	91
300.8	152	51	435.0	279	90
303.9	236	76	438.0	283	94
306.9	240	80	441.1	276	89
310.0	289	93	444.1	308	103
313.0	216	72	447.2	293	95
316.1	140	45	450.2	294	98
319.1	157	52	453.2	263	88
322.2	272	88	456.3	292	94
325.2	265	88	459.3	224	75
328.3	200	65	462.4	242	78
331.3	230	77	465.4	116	39
334.4	75	24	468.5	233	75
337.4	95	32	471.5	282	94
340.5	180	58	474.6	267	86
343.5	203	68	477.6	283	94
346.6	208	67	480.7	282	91
349.6	187	62	483.7	248	83
352.7	144	46	486.8	291	94
355.7	114	38	489.8	285	95
358.8	134	43	492.9	271	87
361.8	282	94	495.9	129	43
364.9	244	79	499.0	173	56
367.9	252	84	502.0	263	88
370.9	170	57	505.1	236	76
374.0	272	88	508.1	277	92
377.0	273	91	511.2	239	77
380.1	264	85	514.2	258	86
383.1	270	90	517.3	216	70
386.2	279	90	520.3	236	79
389.2	217	72	523.4	286	92
392.3	235	76	526.4	290	97
395.3	220	73	529.5	242	78
398.4	258	83	532.5	156	52
401.4	271	90	535.6	180	58
404.5	226	73	538.6	183	61
407.5	207	69			
410.6	215	69		EOH @ 538.6m	

Survey Log LD06-18

UTM Northing (NAD 83): 6161868.656
 UTM Easting (NAD 83): 346771.916
 Elevation (m): 1374.937
 Length (m): 401.4

Depth (ft)	Depth (m)	Azimuth	Corrected Az.	Inclination	Dip	Magnetic
0	0		64.0		-55.0	
77	23.5	42.9	64.9		-54.5	5722
267	81.4	45.4	67.4		-55.6	5813
467	142.3	45.7	67.7		-55.3	5744
687	209.4	48	70.0		-55.2	5759
877	267.3	51	73.0		-53.5	5722
1077	328.3	55.8	77.8		-50.9	5750
no survey below 328.3m						

Diamond Drill Log

LD06-18

Date:

Logged By: DJH

Page 1 / 8

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments													
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG												
0.0	9.1	OB																															Overburden triconed - no core
9.1	48.0	Dd								1		4																				Diorite Dyke med grey, variably magnetic, equigranular, 10-15% mafics, med grained PY in vns w/ QZ, vnlt, <vnlt lt green CL alt'n proximal to PY <vnlt green CL alt'n patches/bands 20.9-22.2: gouge and rubble 29.7-30.0: Biotite Hornfelsed Siliceous Phyllite inclusion 33.9-34.0: dk green, CL altered band loc finer grained variety loc EP alt'n patches lower cnt gradational	
			S1	29.9	46																												
48.0	87.2	Md										3																				Monzonite Dyke lt grey, non-magnetic, wkly porphyritic, 4% mafics, 40% subhedral plag to 4mm w/ 2% feldspar megacrysts to 8X10mm PY as dissems., <vnlt lower cnt gradational	
87.2	107.3	Dd										4																				Diorite Dyke as above 9.1-48.0 MG in rare vns w/ QZ+PY PY in <vnlt, vnlt, rare vns w/ CA or QZ	
107.3	125.6	Md										2																				Monzonite Dyke chilled margins at cnts as above 48.0-87.2 PY in <vnlt, dissems. 2% feldspar megacrysts to 8X10mm rare QZ+MO vnlt 107.6-107.8: strongly fractured w/ gouge lower cnt sheared	

Diamond Drill Log

LD06-18

Date:

Logged By: DJH

Page 4/ 8

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
279.6	283.7	SKp					3	2					1								Ca-Garn+CPx+CA Prograde Skarn
																					w/ 40% CL Retrograde Skarn bands/patches
																					PY as blebs, patches in Retrograde Skarn intervals (up to 8%)
																					MG as patches in Retrograde Skarn intervals (up to 10%)
																					lower cnt sharp, irregular
																					281.7-282.3: CL+MG+PY Retrograde Skarn
																					282.7-283.2: CL+MG+PY Retrograde Skarn w/ remnant Prograde Skarn patches
283.7	287.2	SPbh				5				tr	tr		1								Biotite Hornfelsed Siliceous Phyllite
			S1	286.9	20																biotite loc alt'd to CL+MS
																					PY in <vnlt, vnlt, dissems.
																					lower cnt gradational
287.2	288.7	SPa					1				4		2								Chlorite Altered Siliceous Phyllite
																					w/ 10% Prograde Skarn bands/patches
																					PY as blebs, dissems
																					lower cnt gradational
288.7	291.1	SKr					2	3					5	0.3						0.3	CL+CA+MG+PY Retrograde Skarn
																					w/ 40% Ca-Garn+CPx+CA Prograde Skarn remnants
																					MG as loc patches
																					CP as blebs 290.9-291.1
																					PY as patches/blebs
																					lower cnt gradational
291.1	294.6	SPa					2				4		<1								Chlorite Altered Siliceous Phyllite
			S1	293.3	30																as above 287.2-288.7
																					Biotite Hornfelsed Siliceous Phyllite w/ biotite completely altered to CL
																					w/ 35% bands/patches of Prograde Skarn
																					PY in <vnlt, vnlt, dissems
																					lower cnt gradational
																					291.6-292.3: Prograde Skarn band/patch
294.6	297.8	SKp					5	tr			tr		<1								Ca-Garn+CA+CPx Prograde Skarn
																					loc remnant laminae (Biotite Hornfelsed Siliceous Phyllite protolith?)
																					grades loc to patches of CL altered siliceous phyllite near upper cnt

Diamond Drill Log

LD06-18

Date:

Logged By: DJH

Page 5/ 8

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments		
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG	
																						294.6-297.8 cont'd
																						w/ <10% dark green/black CL Retrograde Skarn patches
																						PY in <vnlts, vnlts, blebs (stronger in Retrograde Skarn)
297.8	302.2	SKp					5	tr			tr		<1								0.3	Ca-Garn Prograde Skarn
																						massive yellow garnet w/ loc CL Retrograde Skarn
																						MG as loc patches
																						PY in vnlts, <vnlts, blebs
																						grades loc to CL altered siliceous phyllite w/ incipient skarn developed
																						HS as loc xtline patches
																						300.3-300.9: CL altered siliceous phyllite w/ incipient skarn
302.2	305.7	Md						tr					<1									Monzonite Dyke
			LC	305.7	62																	upper cnt sharp, irregular
																						w/ loc patches of Prograde Endoskarn
																						PY as dissems
																						w/ 5% feldspar megacrysts to 8X10mm
																						lower cnt sharp, planar
305.7	307.5	SPbh					5	tr			1		<1									Biotite Hornfelsed Siliceous Phyllite
			S1	306.7	70																	loc biotite alt'd to chlorite
																						PY as blebs
																						lower cnt sharp, irregular
																						305.9-306.1: Prograde Skarn patch/band
																						grades loc to Prograde Skarn (incipient skarn development)
307.5	314.8	SKp					5	tr					<1								1	Ca-Garn+CPx+CA Prograde Skarn
																						w/ loc dark green CL Retrograde Skarn patches
																						MG as loc patches
																						HS as loc patches
																						PY in vnlts, <vnlts, blebs (1-5% in Retrograde Skarn patches)
																						lower cnt sharp, irregular
																						311.5-311.9: healed bxia w/ calcite matrix
314.8	316.3	SPbh					5	tr			1		<1	tr								Biotite Hornfelsed Siliceous Phyllite
			S1	326.9	60																	biotite locally alt'd to chlorite

Diamond Drill Log

LD06-18

Date:

Logged By: DJH

Page 6/8

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN	
																				314.8-316.3 cont'd
																				lower cnt not observed
																				PY as blebs
																				loc small patches of garnet (ie incipient skarn)
316.3	323.0	SKp					5	tr				tr								Ca-Garn+CA+/-CPx Prograde Skarn
																				w/ loc dark green/black CL Retrograde Skarn patches
																				HS as loc xtline patches
																				PY in vns w/ QZ, vnlt
																				lower cnt gradational
																				319.9-321.3: QZ+CB replacement (vuggy in part)
323.0	329.4	SPbh					5	tr				<1	tr							Biotite Hornfelses Siliceous Phyllite
			S1	326.9	60															w/ loc bands/patches of Prograde Skarn near upper cnt (ie gradational cnt)
																				slightly darker grey in colour than normal Biotite Hornfelses Siliceous Phyllite
																				(possibly incomplete biotite hornfelsing of siliceous phyllite)
																				PY in <vnlt, blebs
																				PO as blebs
																				325.9-326.2: strongly fractured w/ rubble and gouge
																				lower cnt gradational
329.4	347.9	SKp					5	tr				<1	tr						<1	Ca-Garn+CA+CPx Prograde Skarn
																				w/ loc blebs/patches of dk green/black CL Retrograde Skarn
																				HS as xtline patches
																				MG as loc patches (0-10%)
																				PY as xtline patches
																				QZ as loc patches
																				lower cnt gradational (CP begins @ about 347.1m)
347.9	350.1	SKpm					5	tr				2	<1	12					<1	Mineralized Ca-Garn+CA Prograde Skarn
																				w/ spectacular CP as patches/blebs and interstitial to garnet grains
																				MG as pseudomorphs after HS
																				PO as blebs
																				PY as xtline patches
																				w/ tr dark green/black CL retrograde alt'n
																				lower cnt gradational
																				348.5-348.9: 50% CP

Diamond Drill Log

LD06-18

Date:

Logged By: DJH

Page 7 / 8

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments								
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG							
350.1	354.1	SKpm					2	3						2		2												Incipient Mineralized Ca-Garn+CA+EP Prograde Skarn w/loc EP patches loc wkly laminated (mafic tuff or siliceous phyllite protolith) CP as blebs throughout interval PY as patches/blebs, vnlt lower cnt wkly gradational
354.1	357.8	MT						2						3		1												Mafic Tuff w/ patches/bands mineralized Ca-Garn+CA+EP+CPx(?) Prograde Skarn dark green, wkly laminated, wkly calcareous possible interleaved siliceous phyllite PY as patches/blebs in skarn CP as blebs in skarn
357.8	360.6	SKpm						3	2					3		10												Mineralized Ca-Garn+CA+CPx(?) Prograde Skarn w/ patches/bands of dark green/black CL Retrograde Skarn CP as patches/blebs in prograde and retrograde skarn PY as patches, blebs, stringers lower cnt gradational over 20 cms
360.6	361.7	MT					tr	tr			1		1			3												Mafic Tuff w/ band of nearly massive CP (361.2-361.3) moderately laminated, calcareous, w/ loc dark green CL retrograde alt'n loc patches/bands of Ca-Garn Prograde Skarn PY as blebs, patches lower cnt gradational
361.7	374.7	Md																										Monzonite Dyke pale greenish grey, non-magnetic, <3% mafics wkly porphyritic w/ 4% feldspar phenos to 8X10mm lower cnt sharp, irregular (intrusive)
374.7	381.4	SKp						5	tr					<1		0.3												Ca-Garn+CA+CPx(?) Prograde Skarn w/ loc EP patches loc wkly laminated minor dark green CL retrograde patches/blebs 380.8-381.1: mafic tuff w/ blebs CP lower cnt not observed

Assay Sample Log LD06-18

Page: 1

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Zn
	0.0	210.3	no sample								
369492	210.3	211.8			1.5	100	0.048	1.1	127	609	672
369493	211.8	213.3			1.5	100	0.010	0.3	225	407	25
369494	213.3	214.8			1.5	100	0.005	0.2	122	119	18
369495	214.8	216.3			1.5	100	0.007	0.2	82	187	43
369496	216.3	217.3			1.0	100	0.002	0.3	68	321	12
369497	217.3	218.3			1.0	100	0.067	0.4	181	288	121
	218.3	224.0	no sample								
369498	224.0	225.5			1.5	100	0.068	0.3	162	312	30
369499	225.5	227.0			1.5	100	0.009	0.2	71	211	32
369500			blank				0.002	0.1	1	37	41
369501			CGS-10				1.530	5.8	21	15800	84
369502	227.0	228.5			1.5	100	0.008	0.3	119	317	24
369503	228.5	230.0			1.5	100	0.010	0.3	50	257	32
369504	230.0	231.8			1.8	100	0.019	0.6	99	448	24
	231.8	279.6	no sample								
369505	279.6	281.1			1.5	100	0.009	0.6	139	512	39
369506	281.1	282.6			1.5	100	0.022	0.8	83	776	25
369507	282.6	283.7			1.1	100	0.039	2.0	61	1975	41
	283.7	287.2	no sample								
369508	287.2	288.7			1.5	100	0.023	0.5	15	391	47
369509	288.7	290.2			1.5	100	0.023	1.7	92	1505	42
369510	290.2	291.7			1.5	100	0.230	11.0	90	9500	69
369511	291.7	293.2			1.5	100	0.008	0.4	93	301	26
369512	293.2	294.6			1.4	100	0.017	0.6	8	567	34
369513	294.6	296.2			1.6	100	0.010	0.7	47	551	46
369514	296.2	297.8			1.5	94	0.014	0.7	78	631	30
369515	297.8	299.3			1.5	100	0.008	0.4	140	421	22
369516	299.3	300.8			1.5	100	0.007	0.2	165	226	19
369517	300.8	302.2			1.4	100	0.002	0.2	92	149	24
	302.2	305.7	no sample								
369518	305.7	307.5			1.8	100	0.007	0.2	281	219	23

Assay Sample Log LD06-18

Page: 2

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Zn
369519	307.5	309.0			1.5	100	0.005	0.2	66	198	21
369520			blank				0.002	0.1	1	38	42
369521			CGS-7				0.882	3.7	9	10200	81
369522	309.0	310.5			1.5	100	0.002	0.2	39	173	28
369523	310.5	312.0			1.5	100	0.002	0.3	81	153	31
369524	312.0	313.5			1.5	100	0.002	0.2	185	159	30
369525	313.5	314.8			1.3	100	0.005	0.4	78	275	25
369526	314.8	316.3			1.1	73	0.002	0.4	24	84	48
369527	316.3	317.8			1.5	100	0.002	0.3	93	253	24
369528	317.8	319.3			1.5	100	0.009	0.4	103	371	32
369529	319.3	320.8			1.5	100	0.011	0.6	200	489	26
369530	320.8	322.3			1.5	100	0.020	0.4	407	370	17
369531	322.3	323.8			1.5	100	0.035	0.5	285	446	30
	323.8	329.4	no sample								
369532	329.4	330.9			1.5	100	0.040	0.9	325	531	22
369533	330.9	332.4			1.5	100	0.023	0.5	363	383	20
369534	332.4	333.9			1.5	100	0.002	0.1	289	69	15
369535	333.9	335.4			1.5	100	0.331	0.2	327	9	16
369536	335.4	336.9			1.5	100	0.040	0.4	328	10	15
369537	336.9	338.4			1.5	100	0.178	0.1	327	8	19
369538	338.4	339.9			1.5	100	0.037	0.1	403	12	19
369539	339.9	341.5			1.6	100	0.006	0.1	376	23	16
369541			blank				0.002	0.5	22	114	41
369540			CGS-10				1.915	4.9	22	15500	77
369542	341.5	343.1			1.6	100	0.002	0.2	337	28	15
369543	343.1	344.7			1.6	100	0.007	0.2	548	65	13
369544	344.7	346.3			1.6	100	0.034	0.3	626	171	16
369545	346.3	347.9			1.6	100	0.055	1.7	366	1250	19
369546	347.9	349.1			1.2	100	6.130	122.0	140	82500	2140
369547	349.1	350.1			1.0	100	2.870	51.8	49	31600	337
369548	350.1	351.6			1.5	100	1.540	23.6	50	12700	95
369549	351.6	353.1			1.5	100	1.410	24.6	61	10700	143
369550	353.1	354.6			1.5	100	1.150	25.2	52	10800	145

RQD Log LD06-18

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
9.1			142.3		
11.3	26	12	145.4	207	67
14.3	60	20	148.4	177	59
17.4	95	31	151.5	118	38
20.4	144	48	154.5	72	24
23.5	47	15	157.6	115	37
26.5	44	15	160.6	230	77
29.6	135	44	163.7	220	71
32.6	88	29	166.7	80	27
35.7	107	35	169.8	150	48
38.7	107	36	172.8	270	90
41.8	107	35	175.9	119	38
44.8	160	53	178.9	184	61
47.9	148	48	182.0	270	87
50.9	167	56	185.0	270	90
54.0	170	55	188.1	287	93
57.0	204	68	191.1	252	84
60.1	115	37	194.2	49	16
63.1	232	77	197.2	151	50
66.2	157	51	200.3	241	78
69.2	255	85	203.3	196	65
72.2	147	49	206.4	278	90
75.3	205	66	209.4	232	77
78.3	279	93	212.5	216	70
81.4	241	78	215.5	222	74
84.4	220	73	218.5	172	57
87.5	217	70	221.6	251	81
90.5	120	40	224.6	272	91
93.6	202	65	227.7	229	74
96.6	206	69	230.7	232	77
99.7	158	51	233.8	179	58
102.7	48	16	236.8	215	72
105.8	129	42	239.9	204	66
108.8	96	32	242.9	239	80
111.9	233	75	246.0	262	85
114.9	282	94	249.0	230	77
118.0	200	65	252.1	187	60
121.0	221	74	255.1	213	71
124.1	242	78	258.2	272	88
127.1	138	46	261.2	217	72
130.2	225	73	264.3	100	32
133.2	207	69	267.3	274	91
136.3	180	58	270.4	50	16
139.3	158	53	273.4	66	22
142.3	218	73	276.5	180	58

RQD Log LD06-18

Date: Page: 2

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
276.5					
279.5	110	37			
282.6	279	90			
285.6	160	53			
288.7	172	55			
291.7	276	92			
294.7	226	75			
297.8	396	128			
300.8	115	38			
303.9	266	86			
306.9	185	62			
310.0	269	87			
313.0	244	81			
316.1	169	55			
319.1	263	88			
322.2	300	97			
325.2	144	48			
328.3	136	44			
331.3	209	70			
334.3	256	85			
337.4	203	65			
340.4	268	89			
343.5	255	82			
346.5	278	93			
349.6	299	96			
352.6	280	93			
355.7	244	79			
358.7	287	96			
361.8	282	91			
364.8	242	81			
367.9	232	75			
370.9	230	77			
374.0	141	45			
377.0	251	84			
380.1	285	92			
383.1	122	41			
386.2	38	12			
389.2	114	38			
392.3	0	0			
395.3	0	0			
398.4	26	8			
401.4	0	0			
EOH @ 401.4m					

Diamond Drill Log

LD06-20

Date:

Logged By: DJH

Page 1/ 1

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments					
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG				
0.0	3.7	OB																							Overburden triconed - no core
3.7	29.9	SAc																							Siliceous Argillite dk grey, wkly carbonaceous quartz-muscovite phyllite S1 generally irregular loc calcareous siliceous laminae are loc broken and stretched PY as dissems in siliceous laminae lower cnt sharp, intact, irreg 28.3-29.9: calcareous
			S1	8.2	58																				
			S1	16.4	55																				
			S1	27.0	60																				
29.9	60.0	LSm																							Limestone med blue/grey, massive, recrystallized w/ minor bands of carbonaceous siliceous argillite near upper cnt loc CA vnlt, stringers 41.5-43.8: Fe oxides on fractures 47.3-48.2: Fe oxides on fractures 58.5-58.6: breccia w/ white limestone frags to 5mm and 5% dk grey matrix 58.7-59.1: vuggy limestone w/ Fe oxides on fractures and around vugs
EOH @ 60.0m																									note: hole drilled under "GD" showing

Diamond Drill Log

LD06-23

Date:

Logged By: DJH

Page 1/ 2

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
0.0	4.6	OB																			Overburden triconed - no core
4.6	9.1	SA																			Siliceous Argillite dk grey/black, laminated, quartz+muscovite phyllite lt grey siliceous laminae are generally broken grades loc to calcareous argillite (muscovite+calcite phyllite) tr scorodite and limonite on fractures lower cnt not observed
9.1	10.2	LSm						5													Limestone med blue/grey, massive, wkly recrystallized w/ CA vnlts stwk grades loc to calcareous argillite (muscovite+calcite phyllite) 9.1-9.2: massive, coarse grained PY+SL replacing limestone lower cnt not observed
10.2	11.9	MS-LS						2			60		10								Massive Sulfides massive PY+SL w/ 30% limestone lower cnt not observed
11.9	13.4	LSm						5													Limestone a/a 9.1-10.2 lower cnt gradational
13.4	13.9	MS-LS						2			45		10		5						Massive Sulfides massive PY+SL+AS w/ 40% limestone lower cnt not observed
13.9	16.6	LSm						5			<1	1		1							Limestone white, massive, recrystallized PY as dissems PO+SL as blebs

Diamond Drill Log

LD06-24

Date:

Logged By: DJH

Page 1/ 2

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
0.0	4.6	OB																			Overburden triconed - no core
4.6	11.9	SA																			Siliceous Argillite dk grey/black and lt grey laminated quartz+muscovite phyllite lower cnt gradational
			S1	10.0	50																
11.9	14.9	SAm										5			tr						Very Weakly Mineralized Siliceous Argillite lt grey, altered?, quartz+muscovite phyllite w/ loc argillic alteration? possible shear zone lower cnt not observed PY as patches SL as blebs
14.9	16.4	LS-MS											25								Limestone w/ 25% massive sulfide PY as xline patches 16.4: 20cms oxidized masssive pyrite
16.4	18.8	LSm																			Limestone med grey, massive, recrystallized lower cnt not observed
18.8	19.8	SA																			Siliceous Argillite dk grey quartz+muscovite phyllite
19.8	21.5	SAm											1	<1		<1		<1			Very Weakly Mineralized Siliceous Argillite a/a 11.9-14.9m PY as xline patches PO as blebs SL as blebs AS as xline patches local rhodochrosite lower cnt gradational

Diamond Drill Log LD06-26

Date: Logged By: DJH Page 2/ 5

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments			
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG		
			S1	26.5	45																		11.8-119.0: cont'd
			S1	32.6	42																		PO in vnlt
			FT	33.6	61																		PY as blebs, dissems
			S1	38.6	57																		SL as loc blebs
			S1	44.7	50																		S1 loc contorted w/ siliceous laminae broken and rotated
			S1	51.0	53																		17.5-17.7: massive PO/PY w/ irreg cnts
			S1	57.1	63																		32.8-33.6: strongly broken core w/ gouge
			S1	62.9	40																		51.2: PO+AS+GL+trCP vn @ 47/25mm
			S1	69.1	40																		PO appears to pseudos after PY
			S1	75.3	50																		loc darker grey in colour due to decreasing siliceous content
			S1	81.4	55																		118.7-119.0: PO+AS+SL replacement patches
			S1	87.6	53																		
			S1	93.8	58																		* Is this the west limb of a fold couple with 4B in the syncline or a faulted part of 4B?
			S1	99.9	57																		
			S1	105.8	51																		
119.0	120.0	SA										3	3	5									Siliceous Phyllite
																							partly silicified? quartz+muscovite phyllite
																							w/ vns and replacement patches of PO+PY+AS
																							lower cnt gradational
120.0	183.6	SA											tr	tr									Siliceous Argillite
			S1	127.0	42																		a/a 11.8-119.0
			S1	132.6	63																		120.0-122.0: PO in vnlt, patches, rare vns
			S1	139.4	58																		med to dk grey, laminated quartz+muscovite phyllite
			S1	146.0	45																		grades loc to quartzite w/ 5% muscovite
			S1	152.2	35																		AS as rare xtls aggregates
			S1	160.0	42																		PO in vns, patches, blebs
			S1	166.5	35																		PY in <vnlt, blebs
			S1	172.7	45																		no alteration
			S1	178.9	56																		139.0-139.3: strongly broken w/o gouge
			LC	183.6	66																		145.0-145.4: strongly broken w/o gouge
																							161.8-161.9: massive PO+PY+AS band (vn?)
																							166.6-166.7: strongly broken w/ gouge
																							169.4: AS+PY+marcasite? vn @ 20/12mm
																							169.9-171.3: strongly broken core w/o gouge
																							173.4-174.5: strongly broken core w/ gouge

Diamond Drill Log

LD06-26

Date:

Logged By: DJH

Page 3/ 5

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
																					120.0-183.6: cont'd
																					175.0: AS+PY+PO+tr CP vn
																					175.8-177.2: strongly broken core w/ gouge
																					177.5: kink fold in S1
																					177.2-177.4: marcasite?+PY+AS vns
																					178.1: sand and clay gouge
																					loc "poker chip" cleavage
																					lower cnt sharp, slightly irregular
183.6	183.8	LSm							5												Limestone
			LC	183.8	72																med blue/grey, massive, recrystallized
																					lower cnt sharp, planar
183.8	190.4	MT																			Mafic Tuff
			S1	189.5	50																"dirty" green chlorite+calcite phyllite
																					w/ limestone frags
																					PO as blebs
																					lower cnt sharp, planar (no attitude due to broken core)
190.4	195.4	LSck							5												Limestone
			LC	195.4	70																med blue/grey, massive, recrystallized
																					pale grey calcite "knots" throughout int.
																					lower cnt sharp, planar
195.4	197.9	MT																			Mafic Tuff
			S1	197.2	62																a/a 183.8-190.4
																					"dirty" green chlorite+calcite phyllite
																					w/ limestone frags
																					cnts sharp, irregular
197.9	206.2	LSck							5												Limestone
			LC	206.2	69																med blue/grey, massive, recrystallized
																					w/ calcite "knots" throughout int.
																					w/ interleved mafic tuff to 200.1m
																					lower cnt sharp, planar

Diamond Drill Log

LD06-26

Date:

Logged By: DJH

Page 4/5

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments				
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG			
206.2	212.3	SA											tr									Siliceous Argillite grey, laminated, quartz+muscovite phyllite grades loc to muscovite+quartz phyllite PY in <vnlt>		
			S1	210.3	67																			
212.3	218.6	FT																					Fault Zone strongly broken (sheared) , rubbly core w/ gouge; lost core no attitudes	
218.6	221.2	SA											1		tr		tr						Siliceous Argillite grey quartz+muscovite phyllite SL in vns AS+PY in patch lower cnt sharp, planar	
			S1	221.0	55																			
221.2	221.5	MS											65		25		5						Massive Sulfide Vein	
			LC	221.5	67																		PY+SL+AS massive sulfides w/ 5% quartz gange upper cnt sharp, irreg lower cnt sharp, planar	
221.5	250.3	SA											tr	tr	tr		tr						Siliceous Argillite	
			S1	227.6	55																		grey, laminated, quartz+muscovite phyllite	
			S1	233.9	50																		grades loc to muscovite+quartz and quartz+muscovite+calcite phyllite	
			S1	239.4	59																		loc "spotted" texture w/ pale grey quartz+calcite "spots"	
			S1	245.8	55																		AS as isolated xtls and xtlne patches SL/PY as loc blebs PO as dissems in siliceous laminae grades loc to laminated limestone w/ 10% muscovite grades loc to mafic tuff 224.2-226.0: "spotted" texture w/ 30% quartz+carbonate "spots" 224.1-224.4: PY+AS+/-SL 226.0-226.15: mafic tuff band 242.0-242.2: calcite vn w/ irreg cnts; tr PO	
250.3	260.5	LA											tr											Limy Argillite
			S1	252.1	45																		unit is gradational from siliceous argillite to limestone	

RQD Log LD06-26

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
6.1			139.2		
8.2	38	18	142.3	252	81
11.3	129	42	145.4	114	37
14.3	145	48	148.4	214	71
17.4	32	10	151.5	265	85
20.4	20	7	154.5	225	75
23.5	91	29	157.6	122	39
26.5	70	23	160.6	212	71
29.6	152	49	163.7	94	30
32.6	150	50	166.7	81	27
35.7	133	43	169.8	169	55
38.7	185	62	172.8	64	21
41.8	189	61	175.9	24	8
44.8	165	55	178.9	21	7
47.9	152	49	182.0	62	20
50.9	181	60	185.0	155	52
54.0	233	75	188.1	219	71
57.0	138	46	191.1	135	45
60.1	213	69	194.2	136	44
63.1	218	73	197.2	178	59
66.2	163	53	200.3	253	82
69.2	166	55	203.3	153	51
72.2	77	26	206.4	233	75
75.3	55	18	209.4	48	16
78.3	43	14	212.5	28	9
81.4	73	24	215.5	10	3
84.4	89	30	218.5	141	47
87.5	12	4	221.6	262	85
90.5	95	32	224.6	251	84
93.6	161	52	227.7	260	84
96.6	195	65	230.7	173	58
99.7	222	72	233.8	24	8
102.7	161	54	236.8	61	20
105.8	226	73	239.9	134	43
108.8	212	71	242.9	175	58
111.9	160	52	246.0	87	28
114.9	223	74	249.0	102	34
118.0	75	24	252.1	162	52
121.0	224	75	255.1	131	44
124.1	253	82	258.2	205	66
127.1	214	71	261.2	167	56
130.2	213	69	264.2	62	21
133.2	116	39	267.3	0	0
136.3	133	43			
139.3	72	24		EOH @ 267.3m	

Diamond Drill Log

LD06-27

Date:

Logged By: DJH

Page 1/2

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments		
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG	
0.0	9.8	OB																				Overburden triconed - no core
9.8	14.1	Md										2										Monzonite Dyke lt grey, non-magnetic, w/ 10% mafics w/ chilled margin 11.3-14.1m lower cnt assimilated PY in blebs
14.1	17.1	SA										tr	tr									Siliceous Argillite med grey, laminated, quartz+muscovite phyllite PO in siliceous laminae PY in vnlt, blebs lower cnt sharp, irreg
17.1	18.3	LS																				Limestone med blue/grey, recrystallized w/ tr ca-garnet skarn developed at cnts lower cnt sharp, planar, S1 conformable
			LC	18.3	68		tr		5													
18.3	23.9	SA																				Siliceous Argillite grey, laminated, quartz+muscovite phyllite w/ loc sericite alt'n of muscovite laminae a/a 14.1-17.1 PO as dissems 23.2-23.9: healed bxia zone
			S1	18.6	64				2				<1									
23.9	55.3	Md										2	tr									Monzonite Dyke non-magnetic, non-equigranular, lt grey, w/ 2% mafics w/ 10% anhedral plag to 5mm upper cnt sharp, irreg, w/ chilled margin PY as dissems PO as blebs lower cnt sharp, irreg, x-cuts S1 54.4-54.5: sand and clay gouge

RQD Log LD06-27

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
9.8					
11.3	47	31			
14.3	65	22			
17.4	33	11			
20.4	139	46			
23.5	44	14			
26.5	185	62			
29.6	165	53			
32.6	200	67			
35.7	287	93			
38.7	263	88			
41.8	262	85			
44.8	208	69			
47.9	202	65			
50.9	190	63			
53.9	102	34			
57.0	175	56			
60.0	256	85			
63.1	264	85			
66.1	255	85			
69.2	136	44			
72.2	80	27			
75.3	274	88			
78.3	234	78			
81.4	165	53			
84.4	49	16			
87.5	160	52			
90.5	248	83			
93.6	217	70			
96.6	224	75			
99.6	185	62			
102.7	198	64			
105.8	220	71			
108.8	265	88			
111.9	214	69			
114.9	30	10			
118.0	47	15			
121.0	153	51			
124.0	73	24			
EOH @ 124.0m					

RQD Log LD06-28

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
9.1			142.3		
11.3	95	43	145.4	152	49
14.3	248	83	148.4	223	74
17.4	270	87	151.5	46	15
20.4	216	72	152.8	81	62
23.5	139	45			
26.5	203	68		EOH @ 152.8m	
29.6	116	37			
32.6	235	78			
35.7	227	73			
38.7	154	51			
41.8	226	73			
44.8	202	67			
47.9	230	74			
50.9	203	68			
53.9	178	59			
57.0	148	48			
60.0	83	28			
63.1	163	53			
66.1	133	44			
69.2	141	45			
72.2	270	90			
75.3	206	66			
78.3	244	81			
81.4	255	82			
84.4	231	77			
87.5	238	77			
90.5	162	54			
93.6	237	76			
96.6	225	75			
99.7	248	80			
102.7	262	87			
105.8	275	89			
108.8	241	80			
111.9	204	66			
114.9	182	61			
118.0	71	23			
121.0	125	42			
124.0	197	66			
127.1	225	73			
130.1	190	63			
133.2	161	52			
136.2	247	82			
139.3	187	60			
142.3	192	64			

Survey Log LD06-29

UTM Northing (NAD 83): 6162174.856
UTM Easting (NAD 83): 346833.753
Elevation (m): 1371.231
Length (m): 631.5

Depth (ft)	Depth (m)	Azimuth	Corrected Az.	Inclination	Dip	Magnetic
0	0		46.0		-75.0	
200	61.0	21.8	43.8		75.8	5738
407	124.0	22.8	44.8		-75.8	5746
600	182.9	23	45.0		-76.2	5739
800	243.8	24.6	46.6		-76.2	5747
1007	306.9	25.7	47.7		75.8	5734
1407	428.8	30.1	52.1		-75.7	5728
1607	489.8	32.2	54.2		-75.9	5740
1807	550.7	33.5	55.5		-76.2	5738
2057	626.9	39.2	61.2		-76.2	5723

Diamond Drill Log

LD06-29

Date:

Logged By: DJH

Page 2/11

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments		
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG	
																						61.2-102.7: cont'd
																						85.0: minor rubble and gouge
																						90.8: MO in <vnlts
																						90.8-91.3: strongly broken w/ minor gouge @ 91.3
																						94.4-95.3: strongly broken w/ loc gouge
																						95.8-96.3: strongly broken core w/ gouge throughout
																						98.3: F2 fold couple
102.7	106.3	Dd																				Diorite Dyke
			UC	102.7	20																	med to dk green, fine grained, equigranular, wkly magnetic, w/ 15% mafics
			LC	106.3	16																	PY in <vnlts, vnlts w/ QZ, dissems
																						upper cnt sharp, planar, intact, S1 conformable
																						lower cnt sharp, planar, intact
																						103.4-104.2: monzonite dyke w/ sharp, planar cnts @ 20 deg.; (monzonite is younger than diorite); minor QZ+MO+/-PY vnlts
106.3	110.0	SPbh																				Biotite Hornfelsed Siliceous Phyllite
			S1	108.2	20																	a/a 27.0-56.7
																						PY in vnlts, <vnlts, dissems
110.0	122.7	Dd																				Diorite Dyke
			UC	110.0	20																	a/a 102.7-106.3
			LC	122.7	23																	PY in rare vns, vnlts, <vnlts, dissems
																						upper cnt sharp, planar, intact
																						lower cnt sharp, planar, intact
																						117.3-117.4: feldspar dykelet @ 20 deg
																						118.9-119.0: QZ vn @ 20 deg
122.7	126.6	SPbh																				Biotite Hornfelsed Siliceous Phyllite
																						a/a 27.0-56.7
																						PY in <vnlts w/ loc EP alt'n selvages
																						strongly broken core loc
																						124.7-125.1: diorite dyke w/ upper cnt sharp, planar @ 67 deg; lower cnt sharp planar @ 15 deg.
126.6	128.1	Dd																				Diorite Dyke
			UC	126.6	15																	a/a 102.7-106.3

Diamond Drill Log

LD06-29

Date:

Logged By: DJH

Page 3/ 11

From	To	Rock	Struct	@	CA	Alteration								Mineralization								Comments
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN	MG		
																					126.6-128.1: cont'd	
																					PY in vnlts, <vnlts, patches	
																					loc EP alt'n proximal to PY+QZ vnlts	
																					loc sericite alt'n proximal to PY vnlts	
																					lower cnt not observed due to lost core	
128.1	137.6	SPbh				5				tr		2									Biotite Hornfelses Siliceous Phyllite	
			S1	132.1	40																a/a 27.0-56.7	
																					PY in <vnlts, loc blebs	
																					loc EP alt'n blebs	
																					loc sericite alt'n of biotite rich laminae	
137.6	160.4	Md					trbio														Monzonite Dyke	
																					typical lt green/grey, non-magnetic, non-equigranular, w/ 2% mafics	
																					25-30% plag and <1% euhedral feldspar megacrysts to 8X10mm	
																					darker and finer grained near upper cnt (chilled margin?)	
																					137.6: 10 cms ca-garnet skarn; upper cnt sharp, planar, S1 conformable @ 30 deg	
																					137.9: Biotite Hornfelses Siliceous Phyllite inclusion	
																					lower cnt w/ Biotite Hornfelses Siliceous Phyllite frags over 15cms	
160.4	162.5	SPbh				5	tr					2									Biotite Hornfelses Siliceous Phyllite	
																					a/a 27.0-56.7	
																					PY in patches, vnlts, <vnlts	
																					lower cnt gradational	
																					loc EP alt'n blebs	
162.5	163.3	SKr				1	1	3				5									Calcite+Chlorite Retrograde Skarn	
																					dk green/black chlorite	
																					w/ remnant patches of ca-garnet Prograde Skarn	
																					grades loc to Biotite Hornfelses Siliceous Phyllite	
163.3	166.8	SKr				1	4					10	1								Weakly Mineralized Calcite+Chlorite+/-Epidote Retrograde Skarn	
			LC	166.8	28																dark green/black chlorite	
																					w/ 10-15% remnant ca-garnet Prograde Skarn patches	
																					PY as patches/blebs	
																					CP in vnlts and fine dissems	
																					lower cnt sharp, planar	

Diamond Drill Log

LD06-29

Date:

Logged By: DJH

Page 5/ 11

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
241.8	257.3	Fd					tr						2								Felsite Dyke
			FT	256.8	16																a/a 166.8-189.0
																					grades loc to monzonite
																					PY in <vnlt, dissems, patches
																					minor fracture controlled Prograde Skarn proximal to upper cnt
																					256.1-256.8: broken core w/ gouge
																					upper cnt not observed
																					lower cnt sharp, irreg, x-cuts S1
257.3	261.8	SPbh				5			tr			3									Biotite Hornfelses Siliceous Phyllite
																					a/a 27.0-56.7
																					PY in <vnlt, vnlt, dissems
																					w/ biotite rich laminae loc alt'd to sericite
																					slickensides w/ PY at 261.8m
																					lower cnt not observed
																					257.5-259.3: strongly broken core w/ rubble, gouge and slickensides
261.8	263.0	Md										1									Monzonite Dyke
																					a/a 204.3-235.2 w/ 3% mafics
																					PY in <vnlt, dissems
																					w/ 10cms healed bxia at lower cnt
																					cnt attitudes not observed
263.0	285.4	SPbh				5			tr			3									Biotite Hornfelses Siliceous Phyllite
			S1	267.0	20																a/a 27.0-56.7
			S1	273.4	26																w/ loc sericite alt'n of biotite rich laminae proximal to PY vnlt, <vnlt
			S1	280.1	27																PY in <vnlt, vnlt, dissems
																					cnts not observed
																					263.5-263.8: monzonite dyklet
																					264.4-265.5: monzonite dyklet
																					266.6-266.7: monzonite dyklet
																					268.6-268.9: monzonite dyklet w/ cnts sharp, irregular @ 20 deg
																					275.8-276.4: monzonite dyklet w/ sharp, planar cnts @ 18 deg
																					279.1-279.3: monzonite dyklet w/ irreg lower cnt; upper cnt sharp, planar @ 20 deg

Diamond Drill Log

LD06-29

Date:

Logged By: DJH

Page 6/11

From	To	Rock	Struct	@	CA	Alteration						Mineralization							Comments					
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS		BN	MG			
285.4	287.1	Md								tr		tr	4											Monzonite Dyke
			LC	287.1	15																			med grained, non-magnetic, lt grey, w/o feldspar phenos
																								w/ 4% mafics
																								PY in <vnlt, vnlt, dissems
																								loc QZ+sericite alt'n selvages on PY vnlt, <vnlt
																								upper cnt not observed
																								lower cnt sharp, undulating
287.1	342.2	SPbh				5	tr			tr		3												Biotite Hornfelsed Siliceous Phyllite
			S1	287.6	31																			a/a 27.0-56.7
			FT	292.0	15																			w/ loc bands Prograde Skarn w/ S1 conformable cnts
			S1	294.7	20																			PY in <vnlt, vnlt, dissems
			S1	300.9	20																			loc sericite alt'n of biotite rich laminae proximal to PY vnlt
			S1	307.1	35																			tr EP alt'n blebs
			S1	313.0	20																			291.7-292.3: strongly broken core w/ rubble and gouge
			S1	319.3	10																			295.5-295.7: gouge
			S1	325.1	40																			300.7-300.8: gouge and rubble
			S1	330.9	0																			302.6: gouge and rubble
			S1	336.4	0																			303.8-303.9: cored piece of intrusive (cave-in)
																								313.0-EOL: incipient skarn developed w/ EP patches
																								328.2-328.4: felsite dyke w/ sharp cnts; lower cnt is planar @ 23 deg
																								337.5-338.0: strongly broken core w/ fault gouge
																								339.2-340.7: 15% Prograde Skarn bands and patches
																								340.7-342.2: 5% Prograde Skarn bands/patches; tr EP as blebs
																								lower cnt gradational
342.2	371.8	SKp				tr	5	tr				3												Ca-Garnet+Calcite+C-Px Prograde Skarn
																								massive yellow and lt red/brown ca-garnet
																								w/ xtline calcite patches and lt green diopside?
																								PY in <vnlt, patches
																								grades loc to Biotite Hornfelsed Siliceous Phyllite w/ incipient Prograde Skarn
																								lower cnt gradational
																								loc chlorite Retrograde Skarn alt'n developed
																								tr bright red HE in <vnlt and breccia vns
																								349.5-350.0: Biotite Hornfelsed Siliceous Phyllite w/ incipient Prograde Skarn
																								350.9-351.5: monzonite dyket w/ sharp, intact cnts
																								1% HS as xtline patches

Diamond Drill Log

LD06-29

Date: Logged By: DJH Page 7/ 11

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
																					342.2-371.8: cont'd
																					362.9: tr CP
																					QZ gangue in vns, vnltls locally
371.8	375.1	Md										2									Monzonite Dyke
			UC	371.8	30																med grained, wkly porphyritic, non-magnetic, lt grey
																					w/ 4% mafics
																					w/ finer grained chilled margins
																					upper cnt sharp, planar
																					lower cnt sharp, irreg
																					PY in <vnltls, dissems
																					xenoliths of Biotite Hornfelsed Siliceous Phyllite and Prograde Skarn near upper cnt
375.1	378.4	SKp					5	tr				2									Ca-Garnet+Calcite Prograde Skarn
																					massive yellow w/ minor red/brown ca-garnet
																					xtline calcite patches
																					PY in vnltls w/ QZ, dissems, blebs
																					retrograde chlorite alt'n as selvages loc on QZ+PY vns
378.4	383.5	Md										2									Monzonite Dyke
																					a/a 371.8-375.1
																					PY in <vnltls, dissems
																					darker, finer grained chilled margins
																					cnts are sharp, irreg
383.5	441.9	SKp					5	tr				1	tr								Ca-Garnet+Calcite+C-Px Prograde Skarn
																					massive yellow w/ minor red/brown ca-garnet
																					w/ xtline calcite patches
																					w/ fine grained, lt green diopside? patches
																					loc banded/laminated
																					PY as blebs, dissems, patches
																					1% HS as xtline patches
																					loc retrograde chlorite alt'n patches
																					399.3: banded vn w/ pink carbonate?+clear QZ
																					403.7-405.1: pale green/grey, calcareous patches/bands (Retrograde Skarn?)
																					411.2-411.5: QZ+PY+MG vn; weakly banded
																					CP as blebs, interstitial to garnet grains

Diamond Drill Log

LD06-29

Date:

Logged By: DJH

Page 8/11

From	To	Rock	Struct	@	CA	Alteration								Mineralization								Comments
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN	MG		
																						383.5-441.9: cont'd
																						413.2-413.4: laminated, siliceous argillite band (Quartz+muscovite phyllite)
																						435.7: CP bleb
																						loc bright yellow/green alt'd intervals
																						441.0-441.3: monzonite dyke (chilled phase) w/ sharp, irreg lower cnt; upper cnt not observed
441.9	452.6	Md																				Monzonite Dyke
																						porphyritic, non-magnetic, lt grey, med grained
																						w/ loc pheno to 8X10mm
																						no mineralization
																						slightly chilled margins
																						cnts sharp, irregular
452.6	461.3	SKp					5	tr				1	tr									Ca-Garnet+Calcite+C-Px Prograde Skarn
																						a/a 383.5-441.9
																						w/ loc dk green/black retrograde chlorite blebs/patches
																						PY as patches, blebs, dissem; loc 10-15%
																						<1% HS as xtlne patches
																						454.7: CP patch w/ massive xtlne PY
																						lower cnt gradational
461.3	467.5	SPbh					4	1														Biotite Hornfelses Siliceous Phyllite
			S1	461.7	14																	w/ brown biotite rich laminae defining S1
																						w/ incipient Prograde Skarn developed loc
																						laminated, lt green/brown
																						462.4-463.9: Prograde Skarn w/ remnant laminae indicating siliceous phyllite
																						protolith; gradational cnts; PY in vnlt
																						no mineralization
																						tr HS blebs associated w/ Prograde Skarn patches
																						lower cnt gradational
467.5	475.5	SPbh					5	tr				1										Biotite Hornfelses Siliceous Phyllite
			S1	469.2	17																	w/ brown biotite rich laminae defining S1
																						w/ incipient patches/bands Prograde Skarn
																						PY in <vnlt, patches in Prograde Skarn
																						lower cnt gradational

Diamond Drill Log

LD06-29

Date:

Logged By: DJH

Page 9/ 11

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments					
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG				
475.5	477.2	SKp				1	4						2												Ca-Garnet+Calcite+C-Px Prograde Skarn
																									massive yellow ca-garnet w/ calcite+diopside? patches
																									grades loc to Biotite Hornfelses Siliceous Phyllite w/ incipient Prograde Skarn
																									PY as patches, blebs, vnls
																									lower cnt gradational
477.2	494.3	SPbh				5							tr												Biotite Hornfelses Siliceous Phyllite
			S1	479.7	11																				w/ brown biotite rich laminae defining S1
			S1	485.8	13																				PY in <vnls, dissems
			S1	492.9	30																				lower cnt sharp, irreg
																									492.0-492.5: strongly broken w/ rubble; no gouge
																									492.5-492.8: Prograde Skarn band w/ sharp, irreg cnts
494.3	498.3	SKp					5	tr					2		tr										C-Px+Ca-Garnet+Calcite Prograde Skarn
																									lt green/grey diopside? w/ <10% yellow, ca-garnet patches
																									w/ patches dk green/black retrograde chlorite alt'n
																									grades loc to ca-garnet+calcite Prograde Skarn
																									PY as loc patches (15% near Retrograde Skarn), blebs
																									CP as rare blebs
																									lower cnt gradational
498.3	511.7	SKp					5	tr					<1		tr										Ca-Garnet+Calcite+/-C-Px Prograde Skarn
																									massive yellow >>lt red/brown garnets
																									garnets are loc zoned w/ lt red/brown borders
																									w/ patches of xtline calcite and lt grey/green diopside?
																									loc retrograde chlorite alt'n patches
																									PY in <vnls, patches
																									<1% HS as loc patches
																									CP as rare blebs
																									loc vnls w/ red, earthy HE
511.7	516.9	SPbh					4	1					<1		tr										Biotite Hornfelses Siliceous Phyllite
			UC	511.7	20																				w/ incipient ca-garnet Prograde Skarn
			S1	511.8	20																				511.7-512.3: possible mafic tuff w/ incipient Prograde Skarn
																									w/ 5% patches/bands of ca-garnet Prograde Skarn
																									siliceous laminae are loc broken and stretched (augens?)
																									PY in patches, dissems

Diamond Drill Log

LD06-29

Date:

Logged By: DJH

Page 10/ 11

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
																					511.7-516.9: cont'd
																					lower cnt gradational
																					CP as loc blebs
516.9	548.0	SKp					5	tr					2	tr							Ca-Garnet+Calcite+C-Px Prograde Skarn
																					a/a 489.3-511.7 w/ zoned garnets
																					PY in <vnlt>, patches, interstitial to garnet grains
																					CP as rare blebs
																					<1% HS as xtline patches/blebs
																					loc vnlt> w/ red, earthy HE
																					loc retrograde chlorite alt'n patches
																					loc calcite vnlt>
																					loc QZ patches
																					loc garnet xtl> to 4mm dia in a lt green/grey, fine grained, calcareous matrix
																					(calcite+diopside?)
																					lower cnt gradational
548.0	576.1	SKp					5					tr									C-Px+Ca-Garnet+Calcite Prograde Skarn
																					lt grey/green calcite+diopside?>yellow ca-garnet
																					PY as patches
																					loc red, earthy, HE in <vnlt>
																					loc zoned garnets
																					grades loc to ca-garnet+calcite+/-diopside? w/ patches of xtline HS and 2% PY as patches
																					557.7: purple fluorite
																					574.8: purple fluorite
576.1	577.3	FT																			Prograde Skarn
																					breccia and gouge (fault zone)
577.3	616.0	SKp					5	tr					<1								Ca-Garnet+Calcite+/-C-Px Prograde Skarn
																					massive yellow >>lt red/brown garnets w/ loc white xtline calcite patches
																					w/ loc patches/bands of fine grained, lt green/grey calcite+diopside?
																					loc xtline patches of fluorite
																					loc patches dk green/black retrograde chlorite alt'n
																					PY as blebs, rare patches
																					HS as loc xtline patches

Assay Sample Log LD06-29

Page: 1

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm W	ppm Zn
	0.0	162.3	no sample									
369590	162.3	163.3			1.0	100	0.712	6.2	28	4500	30	46
369591	163.3	164.8			1.5	100	0.932	8.8	33	6980	40	55
369592	164.8	166.3			1.5	100	0.424	4.0	32	3060	20	38
369593	166.3	167.3			1.0	100	0.300	3.4	21	2230	20	50
	167.3	339.2	no sample									
369594	339.2	340.7			1.3	87	0.093	1.7	39	1025	10	83
369595	340.7	342.2			1.5	100	0.029	0.5	59	372	5	41
369596	342.2	343.5			1.3	100	0.136	1.8	59	969	10	44
369597	343.5	345.0			1.5	100	0.027	0.4	111	232	60	34
369598	345.0	346.5			1.4	93	0.041	1.0	80	408	70	37
369599	346.5	348.0			1.5	100	0.010	0.1	1010	126	290	19
369600			blank				0.002	0.1	3	33	5	37
369601			CGS-10				1.710	5.6	21	15600	10	85
369602	348.0	349.6			1.5	94	0.048	0.1	792	62	290	20
369603	349.6	351.1			1.4	93	0.018	0.1	793	231	210	22
369604	351.1	352.6			1.3	87	0.019	0.1	707	129	240	26
369605	352.6	354.1			1.5	100	0.029	0.7	871	408	330	24
369606	354.1	355.7			1.4	88	0.002	0.1	876	22	280	20
369607	355.7	357.2			1.5	100	0.006	0.1	1005	78	330	17
369608	357.2	358.7			1.5	100	0.002	0.1	1230	180	350	16
369609	358.7	360.2			1.5	100	0.007	0.1	1245	30	320	12
369610	360.2	361.8			1.6	100	0.009	0.5	1285	68	360	17
369611	361.8	363.3			1.5	100	0.002	0.1	1465	68	370	14
369612	363.3	364.8			1.5	100	0.002	0.2	1380	65	390	17
369613	364.8	366.3			1.5	100	0.009	0.3	1220	155	250	9
369614	366.3	367.9			1.5	94	0.006	0.4	900	221	180	9
369615	367.9	369.4			1.5	100	0.002	0.3	1365	69	290	18
369616	369.4	370.9			1.5	97	0.189	3.3	1440	259	290	1005
369617	370.9	371.8			0.9	100	0.023	0.5	1185	92	280	70
	371.8	375.1	no sample									
369618	375.1	376.7			1.5	94	0.213	1.8	1345	211	240	767

Assay Sample Log LD06-29

Page: 2

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm W	ppm Zn
369619	376.7	378.4			1.6	94	0.006	0.1	1410	74	310	15
	378.4	383.5	no sample									
369620			blank				0.002	0.1	6	41	5	48
369621			CGS-7				0.876	3.6	12	10200	5	86
369622	383.5	384.7			1.1	92	0.007	0.1	1015	33	180	30
369623	384.7	386.2			1.4	93	0.002	0.1	1040	31	280	23
369624	386.2	387.7			1.5	100	0.006	0.3	946	66	240	19
369625	387.7	389.3			1.4	87	0.002	0.3	748	81	170	15
	389.3	393.7	no sample									
369626	393.7	395.3			1.6	100	0.011	0.1	926	36	250	18
369627	395.3	396.8			1.5	100	0.002	0.2	1130	48	290	15
369628	396.8	398.4			1.5	94	0.002	0.1	1140	10	280	18
369629	398.4	399.9			1.5	100	0.008	0.2	969	14	200	39
369630	399.9	401.4			1.5	100	0.019	0.5	816	225	200	28
369631	401.4	402.9			1.5	100	0.020	0.4	469	172	100	50
369632	402.9	404.4			1.5	100	0.007	0.3	481	152	100	23
369633	404.4	405.9			1.5	100	0.062	1.2	294	677	60	29
369634	405.9	407.5			1.6	100	0.013	0.3	982	138	130	16
369635	407.5	409.0			1.5	100	0.062	1.8	927	1020	130	17
369636	409.0	410.5			1.3	87	0.010	0.3	706	155	110	14
369637	410.5	412.0			1.5	100	0.070	1.4	310	755	60	15
369638	412.0	413.6			1.5	94	0.027	0.9	424	436	80	109
369639	413.6	415.1			1.5	100	0.019	0.4	206	148	30	42
369640	415.1	416.6			1.5	100	0.006	0.2	466	77	110	24
369341			blank				0.002	0.1	1	35	5	39
369642			CGS-10				1.750	4.8	20	15700	5	84
369643	416.6	418.1			1.5	100	0.011	0.3	420	167	100	23
369644	418.1	419.7			1.4	88	0.005	0.3	446	87	110	21
369645	419.7	421.2			1.5	100	0.007	0.2	637	92	130	22
369646	421.2	422.7			1.5	100	0.011	0.5	547	229	130	26
369647	422.7	424.3			1.6	100	0.008	0.6	706	242	160	18
369648	424.3	425.8			1.4	93	0.002	0.4	609	120	140	11
369649	425.8	427.3			1.4	93	0.010	0.4	571	192	170	14

Assay Sample Log LD06-29

Page: 3

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm W	ppm Zn
369650	427.3	428.8			1.4	93	0.009	0.4	589	114	130	31
369651	428.8	430.3			1.4	93	0.026	0.6	551	222	130	19
369652	430.3	431.9			1.4	88	0.006	0.3	677	117	180	14
369653	431.9	433.4			1.5	100	0.011	0.2	596	114	190	19
369654	433.4	434.9			1.4	93	0.007	0.4	665	204	200	19
369655	434.9	436.4			1.5	100	0.002	0.3	635	20	230	14
369656	436.4	438.0			1.5	94	0.007	0.3	719	127	200	18
369657	438.0	439.5			1.5	100	0.008	0.3	803	165	260	18
369658	439.5	441.0			1.4	93	0.010	0.6	966	348	280	15
369659	441.0	441.9			0.9	100	0.002	0.2	412	37	150	29
	441.9	452.6	no sample									
369660	452.6	454.0			1.4	100	0.005	0.4	556	70	180	28
369661	454.0	455.5			1.4	93	0.009	0.3	710	105	250	16
369662	455.5	457.0			1.4	93	0.002	0.2	625	111	260	16
369663	457.0	458.5			1.5	100	0.005	0.4	574	121	180	17
369664	458.5	460.0			1.5	100	0.007	0.2	511	84	140	15
369665	460.0	461.3			1.3	100	0.023	0.4	566	36	120	25
369666	461.3	462.4			1.0	91	0.008	0.2	8	47	5	24
369667	462.4	463.9			1.5	100	0.002	0.3	75	43	20	35
369668	463.9	465.4			1.4	93	0.002	0.1	12	11	5	29
369669	465.4	466.9			1.4	93	0.002	0.1	14	5	5	27
369670	466.9	468.5			1.5	94	0.012	0.3	13	180	5	29
369671	468.5	470.0			1.5	100	0.013	0.5	20	185	10	26
369672	470.0	471.5			1.4	93	0.012	0.5	19	110	5	25
	471.5	475.5	no sample									
369673	475.5	477.2			1.7	100	0.061	0.6	19	285	10	27
	477.2	494.3	no sample									
369674	494.3	495.9			1.6	100	0.009	1.0	21	557	1590	20
369675	495.9	497.4			1.5	100	0.002	0.2	17	42	530	18
369676	497.4	498.9			1.5	100	0.010	0.5	39	206	270	25
369677	498.9	500.4			1.5	100	0.005	0.4	147	116	40	16
369678	500.4	502.0			1.6	100	0.002	0.3	460	29	110	12

Assay Sample Log LD06-29

Page: 4

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm W	ppm Zn
369679	502.0	503.5			1.4	93	0.002	0.3	574	15	190	11
369680			blank				0.002	0.1	4	36	5	40
369681			CGS-7				0.969	3.8	13	9880	5	85
369682	503.5	505.0			1.5	100	0.002	0.2	587	25	160	12
369683	505.0	506.5			1.5	100	0.002	0.1	577	18	160	11
369684	506.5	508.1			1.5	94	0.005	0.4	669	7	240	12
369685	508.1	509.6			1.5	100	0.002	0.3	522	22	160	14
369686	509.6	511.1			1.4	93	0.008	0.5	458	75	130	27
369687	511.1	512.6			1.5	100	0.009	0.5	455	68	130	20
369688	512.6	514.2			1.5	94	0.074	2.2	119	300	10	32
369689	514.2	515.7			1.5	100	0.045	3.5	64	260	20	38
369690	515.7	517.2			1.5	100	0.026	3.1	183	516	60	44
369691	517.2	518.7			1.5	100	0.002	0.4	717	10	250	9
369692	518.7	520.3			1.5	94	0.002	0.1	545	10	190	12
369693	520.3	521.8			1.5	100	0.002	0.2	512	3	190	15
369694	521.8	523.3			1.5	100	0.002	0.2	705	7	200	11
369695	523.3	524.8			1.4	93	0.002	0.1	620	17	190	12
369696	524.8	526.4			1.3	81	0.002	0.3	450	54	110	13
369697	526.4	527.9			1.5	100	0.002	0.2	445	11	100	12
369698	527.9	529.4			1.4	93	0.002	0.3	546	33	90	17
369699	529.4	530.9			1.5	100	0.006	0.4	196	90	90	15
369700	530.9	532.5			1.6	100	0.002	0.2	231	27	90	17
474001	532.5	534.0			1.5	100	0.002	0.1	137	29	50	23
474002	534.0	535.5			1.5	100	0.002	0.4	164	88	60	21
474003	535.5	537.0			1.5	100	0.002	0.2	249	10	90	17
474004	537.0	538.6			1.5	94	0.002	0.2	217	19	60	23
474005	538.6	540.1			1.5	100	0.002	0.1	218	3	60	19
474006	540.1	541.6			1.5	100	0.002	0.2	212	2	50	20
474007	541.6	543.1			1.5	100	0.002	0.3	186	4	220	18
474008	543.1	544.7			1.5	94	0.002	0.1	160	13	100	17
474009	544.7	546.2			1.5	100	0.002	0.2	127	81	50	13
474010	546.2	547.7			1.4	93	0.005	0.3	116	7	40	12
474011	547.7	549.2			1.5	100	0.002	0.3	209	42	80	11

Assay Sample Log LD06-29

Page: 5

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm W	ppm Zn
474012	549.2	550.7			1.5	100	0.014	0.9	194	365	130	12
474013	550.7	552.2			1.5	100	0.006	0.8	214	431	240	16
474014	552.2	553.8			1.5	94	0.002	0.2	154	38	160	15
474015	553.8	555.3			1.5	100	0.005	0.2	117	57	120	15
474016	555.3	556.8			1.5	100	0.002	0.2	86	116	120	19
474017	556.8	558.3			1.5	100	0.002	0.3	148	29	50	20
474018	558.3	559.9			1.5	94	0.007	0.6	118	271	330	19
474019	559.9	561.4			1.5	100	0.015	0.5	268	102	170	20
474020			blank				0.005	0.1	1	36	5	39
474021			CGS-10				1.705	5.3	23	15700	10	87
474022	561.4	562.9			1.5	100	0.081	1.7	186	571	160	24
474023	562.9	564.4			1.5	100	0.002	0.2	186	12	210	25
474024	564.4	566.0			1.5	94	0.002	0.2	236	11	130	33
474025	566.0	567.5			1.5	100	0.002	0.2	208	13	120	34
474026	567.5	569.0			1.5	100	0.002	0.2	186	12	90	33
474027	569.0	570.5			1.5	100	0.002	0.4	197	30	110	28
474028	570.5	572.1			1.4	87	0.002	0.3	216	36	110	33
474029	572.1	573.6			1.5	100	0.002	0.6	132	126	110	40
474030	573.6	575.1			1.4	93	0.002	0.2	185	13	80	28
474031	575.1	576.1			1.0	100	0.007	0.3	111	47	30	48
474032	576.1	577.3			1.1	92	0.002	0.1	334	22	110	25
474033	577.3	578.2			0.9	100	0.002	0.1	302	4	80	21
474034	578.2	579.7			1.5	97	0.002	0.1	435	20	90	21
474035	579.7	581.2			1.5	97	0.002	0.1	418	5	90	18
474036	581.2	582.7			1.5	100	0.002	0.1	263	4	90	17
474037	582.7	584.3			1.5	94	0.002	0.1	431	3	100	16
474038	584.3	585.8			1.5	100	0.002	0.1	460	3	110	16
474039	585.8	587.3			1.5	100	0.002	0.2	455	6	110	14
474040	587.3	588.8			1.5	100	0.002	0.2	439	15	110	11
474041	588.8	590.4			1.5	94	0.002	0.1	541	12	120	10
474042	590.4	591.9			1.3	84	0.002	0.1	683	7	150	8
474043	591.9	593.4			1.3	89	0.002	0.1	649	18	130	12

RQD Log LD06-29

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
18.9			151.5		
20.4	72	48	154.5	266	89
23.5	111	36	157.6	238	77
26.5	130	43	160.6	228	76
29.6	212	68	163.7	145	47
32.6	264	88	66.7	203	-2
35.7	264	85	169.8	213	2
38.7	173	58	172.8	153	51
41.8	173	56	175.9	190	61
44.8	223	74	178.9	208	69
47.9	77	25	182.0	191	62
50.9	147	49	185.0	231	77
53.9	190	63	188.1	201	65
57.0	202	65	191.1	209	70
60.0	94	31	194.1	203	68
63.1	197	64	197.2	66	21
66.1	267	89	200.2	59	20
69.2	252	81	203.3	184	59
72.2	270	90	206.3	152	51
75.3	178	57	209.4	269	87
78.3	179	60	212.4	251	84
81.4	76	25	215.5	125	40
84.4	100	33	218.5	259	86
87.5	50	16	221.6	268	86
90.5	245	82	224.6	265	88
93.6	55	18	227.7	244	79
96.6	61	20	230.7	234	78
99.7	248	80	233.8	83	27
102.7	274	91	236.8	210	70
105.8	209	67	239.9	247	80
108.8	189	63	242.9	222	74
111.9	132	43	246.0	154	50
114.9	169	56	249.0	243	81
118.0	177	57	252.1	278	90
121.0	175	58	255.1	274	91
124.0	172	57	258.2	99	32
127.1	145	47	261.2	48	16
130.1	224	75	264.2	84	28
133.2	245	79	267.3	185	60
136.2	236	79	270.3	230	77
139.3	282	91	273.4	242	78
142.3	299	100	276.4	265	88
145.4	272	88	2179.5	279	0
148.4	253	84	282.5	219	0
151.5	273	88	285.6	172	55

RQD Log LD06-29

Date: Page: 2

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
285.6			419.7		
288.6	188	63	422.7	261	87
291.7	167	54	425.8	265	85
294.7	105	35	428.8	254	85
297.8	80	26	431.9	274	88
300.8	154	51	434.9	295	98
303.9	108	35	438.0	251	81
306.9	194	65	441.0	273	91
310.0	197	64	444.1	238	77
313.0	108	36	447.1	236	79
316.1	156	50	450.2	239	77
319.1	191	64	453.2	203	68
322.2	200	65	456.3	238	77
325.2	154	51	459.3	278	93
328.3	195	63	462.4	265	85
331.3	202	67	465.4	275	92
334.3	212	71	468.5	200	65
337.4	171	55	471.5	287	96
340.4	55	18	474.6	197	64
343.5	155	50	477.6	267	89
346.5	245	82	480.6	214	71
349.6	283	91	483.7	263	85
352.6	263	88	486.7	261	87
355.7	263	85	489.8	204	66
358.7	284	95	492.8	117	39
361.8	257	83	495.9	210	68
364.8	290	97	498.9	296	99
367.9	244	79	502.0	257	83
370.9	245	82	505.0	267	89
374.0	219	71	508.1	285	92
377.0	199	66	511.1	246	82
380.1	189	61	514.2	272	88
381.1	71	71	517.2	268	89
386.2	277	54	520.3	281	91
389.2	196	65	523.3	253	84
392.3	74	24	526.4	237	76
395.3	178	59	529.4	270	90
398.4	297	96	532.5	278	90
401.4	252	84	535.5	288	96
404.4	246	82	538.6	260	84
407.5	268	86	541.6	258	86
410.5	178	59	544.7	263	85
413.6	242	78	547.7	237	79
416.6	273	91	550.7	281	94
419.7	257	83	553.8	260	84

Diamond Drill Log

LD06-30

Date:

Logged By: DJH

Page 1/ 5

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments		
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG	
0.0	40.2	OB																				Overburden triconed - no core
40.2	41.7	LS																				Limestone massive, med grey/white, recrystallized? strongly broken w/ ankerite on fracture surfaces lower cnt not observed
41.7	51.7	LTh	S1	49.3	20																	Lapilli Tuff wkly foliated w/ frags elongated parallel to fol'n; hematitic white, broken QZ vns and vnls loc clay? alt'n related to shearing lower cnt gradational
51.7	53.9	ATa								5												Sericite Altered? Ash Tuff beige, wkly foliated w/ frags elongated parallel to S1 white broken QZ vns lower cnt not observed due to lost core
53.9	54.9	LS																				Limestone massive, med grey/white w/o ankerite on fractures lower cnt not observed rubbly core
54.9	55.4	ATa								5												Sericite Altered? Ash Tuff a/a 51.7-53.9 w/ white QZ vns
55.4	61.9	LTh	LC	61.9	30																	Lapillit Tuff a/a 41.7-51.7; hematitic white, broken QZ vns lower cnt sharp, planar
61.9	64.7	LS																				Limestone massive, med grey/white lower cnt not observed

Diamond Drill Log

LD06-30

Date:

Logged By: DJH

Page 2/5

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments			
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG		
64.7	68.3	LTh																					Lapilli Tuff
			S1	66.0	36																		a/a 41.7-51.7; hematitic
																							65.6-66.5: beige, sericite alt'd?, ash tuff; upper cnt sharp, planar @ 27 deg; lower cnt not observed
																							lower cnt not observed
68.3	69.3	LS																					Limestone
			LC	69.3	26																		dark grey, massive, recrystallized?
																							a/a 53.9-54.9
																							lower cnt sharp, planar
69.3	73.2	LTh																					Lapilli Tuff
			S1	72.9	18																		a/a 41.7-51.7; hematitic
																							72.2-:72.4: rubbly core w/o gouge
																							lower cnt gradational
73.2	77.1	ATa																					Sericite Altered? Ash Tuff
			S1	74.3	40																		a/a 51.7-53.9
			FT	77.1	67																		brecciated, white QZ vns
																							lower cnt gradational
77.1	80.7	LTh																					Lapilli Tuff
																							a/a 41.7-51.7; hematitic; dk maroon colour
																							w/ loc maroon/grey ash tuff interleved
																							lower cnt gradational
80.7	81.4	ATa																					Sericite Altered? Ash Tuff
			LC	81.4	15																		a/a 51.7-53.9
																							w/ loc HE on fractures
																							lower cnt sharp, planar, faulted?
81.4	86.8	ATh																					Ash Tuff
			S1	83.1	25																		wkly foliated; hematitic; maroon coloured
			FT	83.7	30																		white, broken QZ vns
																							83.7-84.1: gouge and breccia
																							w/ loc beige (sericite alt'd?) ash tuff interleved
																							w/ dk red HE on fract (<vnlts); lower cnt gradational

Diamond Drill Log

LD06-30

Date:

Logged By: DJH

Page 3/ 5

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
86.8	90.6	ATa								5											Sericite Altered? Ash Tuff a/a 51.7-53.9 w/ loc red/brown hematite in fractures lower cnt sharp, irreg 88.2-88.4: gouge and soft rubbly core 89.0-89.1: gouge and soft rubbly core
90.6	92.4	LTh	S1	91.7	44																Lapilli Tuff a/a 41.7-51.7; hematitic; maroon colour QZ vn at lower cnt (actual contact not observed)
92.4	97.2	ATh																			Ash Tuff a/a 81.4-86.8; hematitic w/ loc bands of med greenish/grey ash tuff interleaved 92.4-92.7: green/grey ash tuff 93.9-94.0: green/grey ash tuff; cnts sharp, planar @ 27 deg lower cnt gradational
97.2	99.8	ATc																			Weakly Mineralized Ash Tuff med green, chloritic w/ red/brown HE in <vnlt w/ white, broken QZ stwk vns 99.3: bleb of native copper and specks of cinnebar in QZ 99.7: specks of cinnebar in QZ lower cnt gradational
99.8	103.1	ATh-ATc																			Weakly Mineralized Ash Tuff interleaved maroon, hematitic and green chloritic tuff 100.0: specks of cinnebar in QZ 102.9-103.1: rubbly core w/ gouge white fractured QZ vns throughout int. lower cnt not observed (fault?)
103.1	114.8	ATc																			Ash Tuff med green, unfoliated, massive, chloritic w/ red HE in <vnlt white, fractured QZ vn stwk

Diamond Drill Log

LD06-30

Date:

Logged By: DJH

Page 4/5

From	To	Rock	Struct	@	CA	Alteration								Mineralization								Comments			
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN	MG					
																									103.1-114.8: cont'd
																									106.9: distinctive lemon yellow mineral in vn @ 15 deg
																									lower cnt gradational and wkly foliated and laminated
114.8	117.2	ATa							5																Weakly Mineralized Sericite Altered? Ash Tuff
																									a/a 51.7-53.9; beige coloured
																									tr dissemin cinnebar
																									grades loc to maroon, hematitic ash tuff
																									115.4-115.6: rubbly core w/ gouge
																									lower cnt gradational
117.2	119.8	ATh																							Ash Tuff
																									a/a 81.4-86.8; maroon, hematitic
																									lower lower cnt gradational
119.8	129.5	ATc																							Ash Tuff
			S1	124.1	15																				a/a 103.1-114.8; massive to loc laminated and foliated, med green, chloritic
			LC	129.5	15																				w/ 30% hematitic ash tuff interleaved
																									123.3-125.1: laminated and foliated
																									125.8-127.3: hematitic ash tuff
																									126.9-127.0: beige, sericite alt'd ash tuff w/ PY+ tr cinnebar
																									127.3-129.5: laminated and foliated
																									lower cnt sharp, planar
129.5	140.3	ATh																							Ash Tuff
																									a/a 81.4-86.8; maroon, hematitic
																									133.5-133.6: gouge
																									132.1-132.4: beige, sericite alt'd? ash tuff w/ tr cinnebar dissemin
																									136.2-139.3: 0.5m rec'd
																									139.9: rubbly core w/ gouge
																									lower cnt not observed due to lost core
140.3	147.5	ATc																							Ash Tuff
																									a/a 103.1-114.8; massive, med green, chloritic
																									142.3-145.4: 1.7m rec'd w/ rubbly core and sandy gouge
																									lower cnt gradational

RQD Log LD06-30

Date: Page:1

block	RQD (cm)	RQD %	block	RQD (cm)	RQD %
40.2			172.8		
41.8	79	49	175.9	13	4
44.8	190	63	178.9	0	0
47.9	153	49	182.0	25	8
50.9	122	41	185.0	0	0
53.9	75	25	188.1	0	0
57.0	53	17	191.1	133	44
60.0	89	30			
63.1	27	9	EOH @ 191.1 m		
66.1	61	20			
69.2	109	35			
72.2	185	62			
75.3	53	17			
78.3	62	21			
81.4	139	45			
84.4	88	29			
87.5	77	25			
90.5	57	19			
93.6	74	24			
96.6	106	35			
99.7	178	57			
102.7	219	73			
105.8	69	22			
108.8	146	49			
111.9	67	22			
114.9	169	56			
118.0	121	39			
121.0	178	59			
124.0	191	64			
127.1	247	80			
130.1	181	60			
133.2	140	45			
136.2	68	23			
139.3	28	9			
142.3	17	6			
145.4	17	5			
148.4	101	34			
151.5	74	24			
154.5	40	13			
157.6	61	20			
160.6	49	16			
163.7	15	5			
166.7	0	0			
169.8	75	24			
172.8	34	11			

Diamond Drill Log

LD06-31

Date:

Logged By: DJH

Page 1/ 5

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments		
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG	
0.0	9.1	OB																				Overburden triconed - no core
9.1	41.2	LSm							1													Limestone med grey, massive, wkly recrystallized w/ white, calcite stwk vnlt stwk grades loc to breccia w/ 20% white, calcite matrix loc fractures w/ orange/brown oxides or carbonate 36.1: white calcite vn @ 50/30mm vnlt and stringers w/ orange/brown oxide have "bleached" selvages loc strongly broken core w/o gouge or slicks
			VN	36.1	50																	
41.2	41.7	VN																				Calcite Vein orange/white mottled w/ blebs and vnlt of orange/brown oxide or carbonate
41.7	109.3	LSm							1		tr											Limestone a/a 9.1-41.2 loc weakly mineralized w/ PY and cinnebar w/ white calcite stwk vnlt and rare vns w/ loc blebs and smears of yellow/brown oxide? in <vnlt w/ bleached selvages stwk grades loc to incip breccia w/ calcite matrix 43.5-43.7: PY blebs w/ Fe oxide rims and bleached selvages loc strongly broken to rubbly w/o gouge or slicks 61.4: tr cinnebar 67.9: minute specks cinnebar 88.4: threads w/ PY; irreg but approx parallel to core axis 103.8: PY in <vnlt @ 60 deg
109.3	115.2	LSm							1													Limestone massive, med grey, wkly recrystallized w/ intense white calcite stwk vnlt and loc incipient breccia w/ calcite matrix
115.2	127.1	LSm							1		tr											Limestone a/a 9.1-41.2 w/ white calcite stwk vnlt tr orange/brown oxide? in <vnlt, blebs

Diamond Drill Log

LD06-31

Date:

Logged By: DJH

Page 2/5

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments			
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG		
																							115.2-127.1: cont'd
																							loc strongly broken w/o gouge or slicks
																							122.7: tr PY w/ orange/brown oxide in <vnlt
																							124.8: tr PY in <vnlt
127.1	156.0	LSm							1				tr										Limestone
																							med to lt grey, massive, wkly recrystallized
																							w/ weak to mod. calcite stwk vnlt
																							loc incipient breccia w/ calcite matrix
																							loc yellow/orange stain on fractures
																							loc rubbly core w/o gouge or slicks
																							129.7: PY in <vnlt
																							151.5-154.4: abundant bright yellow stain
156.0	161.8	LSm							1														Limestone
																							a/a 9.1-41.2
																							w/ white calcite stwk vnlt
																							loc incipient breccia w/ calcite matrix
161.8	180.5	LSm							1				tr										Limestone
																							a/a 127.1-156.0
																							w/ calcite stwk cnlts
																							no yellow stain; no oxide blebs
																							loc rubbly core w/o gouge or slicks
																							grades loc to med grey limestone w/o calcite vnlt
																							163.3: tr PY as patches containing frags of limestone
																							164.7: tr PY in patches, vns w/ calcite
180.5	182.2	LSm							1														Limestone
																							med grey, massive, wkly recrystallized
																							w/ calcite stwk vnlt
																							no PY mineralization
182.2	184.1	VN																					Calcite Vein
																							white xline calcite
																							upper cnt sharp, irreg
																							lower cnt not observed due to broken core

Diamond Drill Log

LD06-31

Date:

Logged By: DJH

Page 3/ 5

From	To	Rock	Struct	@	CA	Alteration						Mineralization						Comments			
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL		AS	BN	MG
184.1	186.1	LSm							1												Limestone lt grey, massive, wkly recrystallized w/ intense calcite stwk vns
186.1	196.8	LSm							1												Limestone a/a 180.5-182.2 grades loc to lt grey limestone 192.5-196.8: breccia w/ frags of med grey limestone, white xtlne calcite, and pale brown xtlne siderite; <10% med grey calcareous matrix
196.8	197.7	VN	UC	196.8	28																Carbonate Vein coarse xtlne calcite+siderite upper cnt sharp, planar lower cnt not observed due to broken core
197.7	202.8	LSm							1												Limestone a/a 180.5-182.2 loc white calcite vns loc white quartz frags grades loc to lt grey limestone w/ carbonate vns/vnlts 198.9-199.4: caronate vn w/ brecciated cnts
202.8	211.8	VN																			Calcite Vein white, xtlne calcite w/ patches of lt brown siderite upper cnt not observed due to broken core healed breccia at lower cnt; no attitude
211.8	213.9	LSm							1												Limestone med grey, massive, wkly recrystallized w/ white calcite stwk vnlts
213.9	215.6	VN																			Carbonate Vein white calcite+brown siderite cnts sharp, irreg; brecciated upper cnt
215.6	258.7	LSm							1		tr										Limestone med grey, massive, wkly recrystallized

Diamond Drill Log

LD06-31

Date:

Logged By: DJH

Page 4/ 5

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments		
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG	
																						215.6-258.7: cont'd
																						loc strongly broken w/o gouge or slicks
																						w/ white calcite stwk vnlt
																						grades loc to lt grey, massive limestone
																						loc vns/patches of lt brown siderite to 229.8m
																						loc siderite rims on xtline calcite
																						229.5-229.6: PY in <vnlt
																						235.0: tr PY in <vnlt
																						252.7: PY in vnlt and massive in 2cm dia. clast
																						254.7-255.1: calcareous gouge? or ground core
																						255.6: graphite on fracture @ 50 deg
258.7	267.6	LSm						1				tr										Limestone
																						lt grey, massive, wkly recrystallized
																						w/ intense carbonate stwk vnlt
																						grades loc to med grey, massive limestone
																						263.4: tr yellow xtls in <vnlt
																						265.6: tr yellow xtls in <vnlt
																						267.4: PY in <vnlt
																						lower cnt not observed due to broken core
267.6	281.6	LSm						1				tr										Limestone
																						med grey, massive, wkly recrystallized
																						w/ weak calcite stwk vnlt
																						lower cnt not observed due to broken core
																						271.6-271.8: PY in <vnlt
																						273.0-281.6: loc white calcite and lt brown siderite vns
281.6	287.1	LSm						1														Limestone
																						med grey, massive, wkly recrystallized
																						w/ numerous calcite+siderite vns/patches
																						local breccia w/ xtline carbonate matrix
287.1	303.9	LSm						1				tr										Limestone
			SL	297.0	50																	med grey, massive, wkly recrystallized
																						w/ loc calcite+siderite vns
																						mod to weak calcite stwk vnlt (loc intense)

Assay Sample Log

LD06-31

Page: 1

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
	0.0	9.1	no sample									
181001	9.1	11.3			1.9	86	0.002	0.1	4	2	11	20
181002	11.3	12.8			1.5	100	0.002	0.1	6	2	7	20
181003	12.8	14.3			1.5	100	0.002	0.1	8	1	3	20
181004	14.3	15.8			1.3	87	0.002	0.1	11	2	6	22
181005	15.8	17.4			1.3	81	0.005	0.1	5	1	4	23
181006	17.4	18.9			1.5	100	0.002	0.1	11	2	6	22
181007	18.9	20.4			1.5	100	0.002	0.1	7	1	6	20
181008	20.4	21.9			1.5	100	0.002	0.2	2	2	3	22
181009	21.9	23.5			1.5	94	0.002	0.2	7	1	4	27
181010	23.5	25.0			1.5	100	0.002	0.1	1	0.5	3	14
181011	25.0	26.5			1.5	100	0.002	0.2	9	1	3	21
181012	26.5	28.0			1.5	100	0.002	0.1	1	1	2	16
181013	28.0	29.6			1.5	94	0.002	0.1	1	1	2	15
181014	29.6	31.1			1.5	100	0.002	0.1	5	1	3	13
181015	31.1	32.6			1.5	100	0.002	0.1	1	1	3	9
181016	32.6	34.1			1.4	93	0.002	0.1	2	1	4	10
181017	34.1	35.7			1.5	94	0.002	0.2	3	1	2	9
181018	35.7	37.2			1.5	100	0.002	0.1	8	1	2	9
181019	37.2	38.7			1.5	100	0.002	0.2	4	1	4	16
181020	38.7	40.2			1.5	100	0.002	0.2	11	1	3	32
181021	40.2	41.8			1.5	94	0.002	0.1	5	2	8	23
181022	41.8	43.3			1.5	100	0.002	0.2	2	2	21	30
181023	43.3	44.8			1.5	100	0.002	0.1	5	1	4	31
181024	44.8	46.3			1.5	100	0.002	0.1	4	1	4	10
181025	46.3	47.9			1.5	94	0.002	0.1	5	0.5	2	6
181026	47.9	49.4			1.5	100	0.002	0.1	3	1	3	7
181027	49.4	50.9			1.5	100	0.002	0.1	3	1	3	9
181028	50.9	52.4			1.5	100	0.002	0.1	1	0.5	3	11
181029	52.4	53.9			1.5	100	0.002	0.1	1	1	2	9
181030	53.9	55.4			1.5	100	0.002	0.2	4	1	1	15
181031	55.4	57.0			1.5	94	0.002	0.1	1	1	1	13

Assay Sample Log

LD06-31

Page: 2

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
181032	57.0	58.5			1.5	100	0.002	0.1	3	1	2	10
181033	58.5	60.0			1.5	100	0.002	0.1	1	0.5	2	10
181034	60.0	61.5			1.5	100	0.002	0.1	1	1	4	12
181035	61.5	63.1			1.6	100	0.002	0.2	7	1	3	11
181036	63.1	64.6			1.5	100	0.002	0.2	4	1	3	14
181037	64.6	66.1			1.5	100	0.002	0.1	1	1	2	14
181038	66.1	67.6			1.5	100	0.002	0.1	1	1	4	15
181039	67.6	69.2			1.6	100	0.002	0.1	1	1	17	18
181040	69.2	70.7			1.5	100	0.002	0.1	4	1	4	12
181041	70.7	72.2			1.5	100	0.002	0.2	6	1	12	15
181042	72.2	73.7			1.5	100	0.002	0.1	5	2	6	22
181043	73.7	75.3			1.6	100	0.002	0.1	1	1	2	15
181044	75.3	76.8			1.5	100	0.002	0.2	8	1	14	15
181045	76.8	78.3			1.5	100	0.002	0.1	6	1	3	16
181046	78.3	79.8			1.5	100	0.002	0.2	2	1	3	12
181047	79.8	81.4			1.4	87	0.002	0.1	5	1	2	10
181048	81.4	82.9			1.4	93	0.002	0.1	11	1	2	20
181049	82.9	84.4			1.5	100	0.002	0.2	8	3	3	23
181050	84.4	85.9			1.5	100	0.002	0.2	2	1	2	10
181051	85.9	87.5			1.6	100	0.002	0.3	6	1	1	12
181052	87.5	89.0			1.5	100	0.010	0.1	12	1	2	9
181053	89.0	90.5			1.5	100	2.600	0.2	12	1	2	7
181054	90.5	92.0			1.5	100	0.069	0.1	1	1	2	9
181055	92.0	93.6			1.4	88	0.170	0.2	4	1	2	10
181056	93.6	95.1			1.5	100	0.046	0.2	9	1	2	8
181057	95.1	96.6			1.5	100	0.022	0.1	1	1	2	6
181058	96.6	98.1			1.5	100	0.039	0.2	12	2	3	11
181059	98.1	99.7			1.4	87	0.029	0.2	2	1	3	8
181060	99.7	101.2			1.5	100	0.045	0.1	1	1	2	9
181061	101.2	102.7			1.5	100	0.681	0.2	6	3	3	11
181062	102.7	104.2			1.5	100	0.014	0.2	9	1	2	11
181063	104.2	105.8			1.5	94	1.160	0.2	4	2	6	18
181064	105.8	107.3			1.5	100	0.018	0.2	11	2	2	13

Assay Sample Log

LD06-31

Page: 3

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
181065	107.3	108.8			1.5	100	0.013	0.2	1	1	2	13
181066	108.8	110.3			1.5	100	0.055	0.2	1	2	2	12
181067	110.3	111.9			1.6	100	0.010	0.1	13	1	2	12
181068	111.9	113.4			1.4	93	0.007	0.1	1	0.5	1	10
181069	113.4	114.9			1.5	100	0.008	0.1	1	0.5	2	13
181070	114.9	116.4			1.4	93	0.012	0.1	1	0.5	0.5	10
181071	116.4	118.0			1.5	94	0.024	0.1	1	0.5	2	11
181072	118.0	119.5			1.5	100	0.012	0.1	1	0.5	0.5	12
181073	119.5	121.0			1.5	100	0.002	0.1	8	0.5	4	10
181074	121.0	122.5			1.3	87	0.002	0.2	1	0.5	4	10
181075	122.5	124.0			1.4	93	0.013	0.1	1	0.5	2	10
181076	124.0	125.5			1.5	100	0.014	0.1	1	0.5	0.5	11
181077	125.5	127.1			1.6	100	0.018	0.1	3	0.5	1	11
181078	127.1	128.6			1.5	100	0.007	0.1	1	0.5	1	11
181079	128.6	130.1			1.5	100	0.002	0.1	1	0.5	1	9
181080	130.1	131.6			1.3	87	0.002	0.1	1	0.5	0.5	10
181081	131.6	133.2			1.3	81	0.002	0.1	1	0.5	1	14
181082	133.2	134.7			1.4	93	0.002	0.1	4	4	0.5	11
181083	134.7	136.2			1.5	100	0.002	0.1	1	0.5	0.5	9
181084	136.2	137.7			1.5	100	0.002	0.1	1	4	0.5	10
181085	137.7	139.3			1.6	100	0.002	0.1	1	0.5	0.5	8
181086	139.3	140.8			1.4	93	0.002	0.1	3	0.5	3	7
181087	140.8	142.3			1.4	93	0.002	0.1	1	0.5	1	7
181088	142.3	143.8			1.4	93	0.002	0.1	2	0.5	0.5	7
181089	143.8	145.4			1.5	94	0.002	0.1	1	0.5	2	7
181090	145.4	146.9			1.4	93	0.002	0.1	1	0.5	3	7
181091	146.9	148.4			1.5	100	0.002	0.1	5	0.5	2	8
181092	148.4	149.9			1.4	93	0.002	0.1	9	0.5	2	12
181093	149.9	151.5			1.6	100	0.002	0.1	1	1	5	14
181094	151.5	153.0			1.3	87	0.002	0.1	1	0.5	0.5	18
181095	153.0	154.5			0.8	53	0.002	0.1	6	0.5	1	13
181096	154.5	156.0			1.4	93	0.002	0.1	1	0.5	2	10
181097	156.0	157.6			1.4	88	0.002	0.1	1	0.5	1	8

Assay Sample Log

LD06-31

Page: 4

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
181098	157.6	159.1			1.5	100	0.002	0.1	1	0.5	0.5	8
181099	159.1	160.6			1.4	93	0.002	0.1	1	0.5	0.5	9
181100	160.6	162.1			1.5	100	0.002	0.1	1	0.5	1	9
181101	162.1	163.7			1.5	94	0.002	0.1	8	0.5	1	18
181102	163.7	165.2			1.5	100	0.002	0.1	15	0.5	3	19
181103	165.2	166.7			1.5	100	0.002	0.1	1	0.5	2	12
181104	166.7	168.2			1.5	100	0.002	0.2	6	1	1	9
181105	168.2	169.8			1.3	81	0.002	0.1	1	1	2	9
181106	169.8	172.8			1.0	33	0.002	0.2	2	1	2	10
181107	172.8	175.9			0.4	13	0.002	0.1	1	1	2	7
181108	175.9	177.4			1.1	73	0.002	0.1	2	0.5	1	5
181109	177.4	178.9			1.0	67	0.002	0.2	1	0.5	0.5	6
181110	178.9	180.4			1.2	80	0.002	0.1	1	2	3	9
181111	180.4	182.0			1.2	75	0.002	0.2	1	1	2	11
181112	182.0	183.5			0.9	60	0.002	0.2	13	2	9	59
181113	183.5	185.0			0.7	47	0.002	0.1	11	1	4	6
181114	185.0	186.5			1.3	87	0.002	0.1	5	1	2	10
181115	186.5	188.1			1.5	94	0.042	0.2	9	1	2	11
181116	188.1	189.6			1.5	100	0.002	0.2	1	1	2	8
181117	189.6	191.1			1.5	100	0.002	0.2	6	1	2	9
181118	191.1	192.6			1.4	93	0.002	0.2	2	1	2	12
181119	192.6	194.1			1.4	93	0.444	0.2	1	4	5	29
181120	194.1	197.2			1.5	48	0.011	0.2	1	2	5	20
181121	197.2	198.7			1.5	100	0.048	0.1	3	4	6	31
181122	198.7	200.2			1.5	100	0.031	0.1	1	3	3	14
181123	200.2	201.7			1.5	100	0.031	0.2	1	3	2	29
181124	201.7	203.3			1.4	87	0.002	0.2	5	2	2	77
181125	203.3	206.3			1.9	63	0.002	0.1	1	1	2	14
181126	206.3	207.8			1.2	80	0.002	0.2	1	2	3	37
181127			no sample									
181128	207.8	210.9			2.4	77	0.009	0.5	3	9	1	95
181129	210.9	212.4			1.5	100	0.002	0.1	7	4	2	46
181130	212.4	213.9			1.5	100	0.002	0.1	1	1	0.5	12

Assay Sample Log

LD06-31

Page: 5

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
181131	213.9	215.5			1.3	81	0.002	0.1	4	2	1	52
181132	215.5	217.0			1.3	87	0.002	0.1	1	1	1	13
181133	217.0	218.5			1.4	93	0.005	0.1	3	2	6	25
181134	218.5	220.0			1.5	100	0.012	0.1	1	1	0.5	28
181135	220.0	221.6			1.5	94	0.002	0.1	1	1	2	14
181136	221.6	223.1			1.5	100	0.002	0.1	1	1	0.5	11
181137	223.1	224.6			1.5	100	0.005	0.1	1	1	1	8
181138	224.6	226.1			1.4	93	0.002	0.1	2	1	1	7
181139	226.1	227.7			1.1	69	0.002	0.1	1	1	0.5	8
181140	227.7	229.2			1.1	73	0.002	0.1	1	1	2	8
181141	229.2	230.7			1.0	67	0.002	0.1	17	1	1	9
181142	230.7	233.8			1.1	35	0.002	0.1	1	0.5	0.5	10
181143	233.8	235.3			0.9	60	0.002	0.1	1	1	2	13
181144	235.3	236.8			1.0	67	0.002	0.1	1	1	1	14
181145	236.8	239.9			0.5	16	0.002	0.1	1	0.5	0.5	13
181146	239.9	242.9			1.0	33	0.002	0.1	1	1	0.5	25
181147	242.9	244.4			0.8	53	0.002	0.1	1	1	0.5	25
181148	244.4	246.0			0.7	44	0.002	0.1	1	0.5	0.5	17
181149	246.0	247.5			1.2	80	0.002	0.1	1	1	1	55
181150	247.5	249.0			1.2	80	0.002	0.1	1	1	1	23
181151	249.0	252.1			0.2	6	0.002	0.1	2	1	0.5	16
181152	252.1	253.6			1.1	73	0.002	0.1	4	1	4	22
181153	253.6	255.1			1.2	80	0.002	0.1	3	1	2	15
181154	255.1	256.6			1.4	93	0.005	0.1	1	0.5	1	11
181155	256.6	258.2			1.5	94	0.002	0.1	1	1	1	19
181156	258.2	259.7			1.3	87	0.005	0.1	1	1	2	13
181157	259.7	261.2			1.2	80	0.002	0.1	1	1	0.5	17
181158	261.2	262.7			1.4	93	0.017	0.1	1	2	1	18
181159	262.7	264.2			1.3	87	0.015	0.1	1	1	2	14
181160	264.2	265.7			1.0	67	0.002	0.1	1	1	1	7
181161	265.7	267.3			1.1	69	0.002	0.1	1	0.5	1	9
181162	267.3	270.3			1.0	33	0.002	0.1	1	1	0.5	10
181163	270.3	271.8			1.2	80	0.002	0.1	1	0.5	1	10

RQD Log LD06-31

Date: Page:1

block	rqd (in)	RQD (cm)	RQD %	block	rqd (in)	RQD (cm)	RQD %
9.1				142.3			
11.3	40.0	102	46	145.4	56.0	142	18
14.3	37.5	95	32	148.4	24.0	61	8
17.4	60.0	152	49	151.5	82.5	210	27
20.4	88.5	225	75	154.5	18.0	46	6
23.5	58.0	147	48	157.5	85.5	217	29
26.5	33.0	84	28	160.6	67.0	170	22
29.6	47.0	119	39	163.7	65.5	166	21
32.6	31.5	80	27	166.7	52.5	133	18
35.7	50.5	128	41	169.8	32.0	81	10
38.7	88.5	225	75	172.8	0.0	0	0
41.8	73.5	187	60	175.9	0.0	0	0
44.8	84.5	215	72	178.9	25.0	64	8
47.9	25.5	65	21	182.0	33.5	85	11
50.9	70.0	178	59	185.0	25.0	64	8
53.9	29.5	75	25	188.1	38.0	97	12
57.0	36.0	91	29	191.1	51.0	130	17
60.0	13.0	33	11	194.1	46.5	118	16
63.1	24.0	61	20	197.2	29.0	74	9
66.1	85.0	216	72	200.2	74.0	188	25
69.2	24.0	61	20	203.3	62.5	159	20
72.2	50.0	127	42	206.3	17.0	43	6
75.3	5.0	13	4	209.4	51.5	131	17
78.3	21.5	55	18	212.4	66.5	169	22
81.4	22.0	56	18	215.5	58.0	147	19
84.4	57.0	145	48	218.8	38.0	97	12
87.5	32.0	81	26	221.6	68.5	174	24
90.5	62.0	157	52	224.6	66.0	168	22
93.6	27.5	70	23	227.7	40.5	103	13
96.6	61.5	156	52	230.7	21.5	55	7
99.7	58.5	149	48	233.8	4.0	10	1
102.7	76.5	194	65	236.8	10.0	25	3
105.8	61.0	155	50	239.9	0.0	0	0
108.8	75.5	192	64	242.9	0.0	0	0
111.9	70.0	178	57	246.0	11.0	28	4
114.9	53.0	135	45	249.0	24.5	62	8
118.0	25.0	64	20	252.1	0.0	0	0
121.0	67.5	171	57	255.1	50.5	128	17
124.0	48.0	122	41	258.2	85.0	216	27
127.1	70.0	178	57	261.2	32.0	81	11
130.1	27.5	70	23	264.2	35.0	89	12
133.2	13.5	34	11	267.3	8.0	20	3
136.2	15.0	38	13	270.3	4.0	10	1
139.3	34.5	88	28	273.4	27.0	69	9
142.3	8.5	22	7	276.4	0.0	0	0

Diamond Drill Log

LD06-32

Date:

Logged By: DJH

Page 3/ 4

From	To	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
																					160.6-173.3: cont'd
																					w/o orange/brown oxide? patches
																					loc bright yellow, xtline, very soft mineral on fract (<vnlt)
																					lower cnt gradational
																					160.7: PY in irreg, discontinuous vnlt
173.3	218.9	LSm							1			tr									Limestone
			FT	192.8	67																lt to med grey, massive, wkly recrystallized
			FT	193.0	58																a/a 160.6-173.3
																					w/o distinct yellow mineral
																					w/ weak to intense calcite stwk vnlt (grades loc to incipient breccia)
																					173.6-173.8: PY in vnlt
																					loc rubbly core w/ loc fault gouge
																					178.1: PY in <vnlt
																					184.0: PY in <vnlt
																					192.8: fault w/ 5mm gouge
																					193.0: fault w/ 5mm gouge
																					195.3: tr cinnebar as specks
																					203.3: PY in irreg <vnlt
																					204.4: PY in <vnlt
																					207.0: PY in irreg, discontinuous vnlt/gash
218.9	221.2	Fd																			Felsite Dyke
			UC	218.9	40																pale cream colour, aphanitic, w/ <2% QZ phenos to 1mm dia
			LC	221.2	40																upper cnt sharp, planar, banded
																					lower cnt sharp, planar, w/o banding
																					no mineralization or alt'n
																					218.9-219.5: partially banded; lt orange/brown colour
221.2	248.2	LSm							1			tr									Limestone
																					med to dark grey, massive, wkly recrystallized
																					w/ weak to intense calcite stwk vnlt
																					loc rubbly core w/o gouge or slicks
																					tr orange/brown oxide? blebs
																					226.3: PY in <vnlt

Assay Sample Log

LD06-32

Page: 1

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
	0.0	9.8	no sample									
181181	9.8	11.3			0.9	60	0.002	0.1	10	6	5	28
181182	11.3	12.8			1.3	87	0.002	0.1	16	0.5	5	17
181183	12.8	14.3			1.4	93	0.002	0.1	7	0.5	4	12
181184	14.3	15.8			1.1	73	0.002	0.1	11	0.5	2	5
181185	15.8	17.4			1.1	69	0.002	0.1	11	0.5	4	14
181186	17.4	18.9			1.4	93	0.002	0.1	12	1	5	22
181187	18.9	20.4			1.3	87	0.002	0.1	12	0.5	6	22
181188	20.4	21.9			1.4	93	0.002	0.1	19	0.5	15	39
181189	21.9	23.5			1.3	81	0.002	0.1	10	0.5	8	24
181190	23.5	25.0			1.4	93	0.002	0.1	6	0.5	4	15
181191	25.0	26.5			1.4	93	0.002	0.1	12	1	5	27
181192	26.5	28.0			1.3	87	0.002	0.1	8	0.5	2	19
181193	28.0	29.6			1.1	69	0.002	0.1	19	0.5	19	26
181194	29.6	31.1			1.3	87	0.002	0.1	9	0.5	23	17
181195	31.1	32.6			1.4	93	0.002	0.1	8	0.5	34	17
181196	32.6	34.1			0.9	60	0.002	0.1	15	2	167	29
181197	34.1	35.7			1.0	62	0.002	0.1	9	0.5	148	9
181198	35.7	37.2			0.9	60	0.002	0.1	10	1	87	15
181199	37.2	38.7			0.8	53	0.002	0.1	7	0.5	5	16
181200	38.7	40.2			1.2	80	0.002	0.1	11	0.5	8	24
181201	40.2	41.8			1.1	69	0.002	0.1	21	0.5	4	22
181202	41.8	43.3			1.3	87	0.002	0.1	1	0.5	6	24
181203	43.3	44.8			1.2	80	0.002	0.1	5	0.5	9	17
181204	44.8	46.3			1.2	80	0.002	0.1	18	0.5	14	37
181205	46.3	47.9			1.3	81	0.002	0.1	12	0.5	4	18
181206	47.9	49.4			1.1	73	0.002	0.1	6	0.5	2	14
181207	49.4	50.9			1.1	73	0.002	0.1	11	0.5	4	16
181208	50.9	52.4			1.2	80	0.002	0.1	6	0.5	5	11
181209	52.4	53.9			1.4	93	0.008	0.1	13	0.5	5	19
181210	53.9	55.4			1.4	93	0.006	0.1	14	0.5	6	38
181211	55.4	57.0			1.4	87	0.002	0.1	1	0.5	18	55

Assay Sample Log

LD06-32

Page: 2

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
181212	57.0	58.5			1.2	80	0.002	0.1	2	0.5	29	49
181213	58.5	60.0			1.5	100	0.002	0.1	1	0.5	7	19
181214	60.0	61.5			1.0	67	0.002	0.1	6	0.5	12	51
181215	61.5	63.1			0.8	50	0.007	0.1	31	0.5	23	46
181216	63.1	64.6			1.2	80	0.007	0.1	11	32	5	17
181217	64.6	66.1			1.0	67	0.002	0.1	3	0.5	7	35
181218	66.1	67.6			1.4	93	0.002	0.1	10	0.5	10	39
181219	67.6	69.2			1.4	87	0.002	0.1	2	0.5	16	57
181220	69.2	70.7			1.1	73	0.005	0.1	7	0.5	10	35
181221	70.7	72.2			1.4	93	0.009	0.1	10	0.5	3	13
181222	72.2	73.7			1.2	80	0.006	0.1	5	0.5	8	20
181223	73.7	75.3			1.2	75	0.002	0.1	5	0.5	1	12
181224	75.3	75.9			0.6	100	0.002	0.1	31	0.5	10	19
181225	75.9	77.7			1.7	94	0.009	0.1	177	1	101	111
181226	77.7	79.8			1.7	81	0.002	0.1	17	0.5	7	53
181227	79.8	81.4			1.5	94	0.012	0.1	37	0.5	48	101
181228	81.4	82.9			1.2	80	0.018	0.1	24	1	18	36
181229	82.9	84.4			1.4	93	0.092	5.2	804	18	279	261
181230	84.4	85.9			1.5	100	0.027	0.1	302	0.5	34	62
181231	85.9	87.5			1.3	81	0.027	0.1	13	0.5	8	19
181232	87.5	89.0			1.2	80	0.002	0.1	1	0.5	4	8
181233	89.0	90.5			1.3	87	0.005	0.1	1	0.5	4	11
181234	90.5	92.0			1.3	87	0.009	0.1	15	0.5	6	18
181235	92.0	93.6			1.5	94	0.007	0.1	17	0.5	9	16
181236	93.6	95.1			1.3	87	0.002	0.1	3	0.5	3	9
181237	95.1	96.6			1.4	93	0.002	0.1	12	0.5	4	14
181238	96.6	98.1			1.3	87	0.005	0.1	5	0.5	3	17
181239	98.1	99.7			1.3	81	0.006	0.1	2	0.5	5	15
181240	99.7	101.2			1.3	87	0.007	0.1	7	0.5	10	36
181241	101.2	102.7			1.5	100	0.010	0.1	2	0.5	5	22
181242	102.7	104.2			1.4	93	0.005	0.1	4	0.5	4	10
181243	104.2	105.8			1.4	88	0.008	0.1	4	0.5	1	9
181244	105.8	107.3			1.5	100	0.009	0.1	6	0.5	2	12

Assay Sample Log

LD06-32

Page: 3

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
181245	107.3	108.8			1.4	93	0.017	0.1	3	0.5	5	23
181246	108.8	110.3			1.5	100	0.006	0.1	3	0.5	2	13
181247	110.3	111.9			1.4	87	0.005	0.1	1	2	3	26
181248	111.9	113.4			1.4	93	0.005	0.1	3	1	2	15
181249	113.4	114.9			1.4	93	0.005	0.1	6	1	2	14
181250	114.9	116.4			1.1	73	0.005	0.1	2	0.5	2	14
181251	116.4	118.0			1.2	75	0.002	0.1	4	1	1	20
181252	118.0	119.5			1.5	100	0.002	0.1	2	0.5	2	38
181253	119.5	121.0			1.2	80	0.007	0.1	5	1	1	13
181254	121.0	122.5			1.3	87	1.865	0.1	6	1	3	11
181255	122.5	124.0			1.5	100	0.607	0.1	1	1	2	9
181256	124.0	125.5			1.5	100	0.028	0.1	3	1	1	9
181257	125.5	127.1			1.4	88	0.021	0.1	5	2	2	12
181258	127.1	128.6			1.5	100	0.015	0.1	2	2	2	16
181259	128.6	130.1			1.3	87	0.002	0.1	1	0.5	2	10
181260	130.1	131.6			1.5	100	0.002	0.1	1	0.5	1	9
181261	131.6	133.2			1.3	81	0.010	0.1	1	1	1	37
181262	133.2	134.7			1.4	93	0.090	0.1	2	1	1	17
181263	134.7	136.2			1.5	100	0.202	0.1	4	1	2	14
181264	136.2	137.7			1.4	93	0.047	0.1	4	1	1	12
181265	137.7	139.3			1.4	87	0.077	0.1	4	0.5	1	11
181266	139.3	140.8			1.5	100	0.034	0.1	6	0.5	1	11
181267	140.8	142.3			1.3	87	0.011	0.1	6	0.5	2	15
181268	142.3	143.8			1.5	100	0.006	0.1	6	1	1	14
181269	143.8	145.4			1.3	81	0.005	0.1	4	0.5	1	13
181270	145.4	146.9			1.1	73	0.005	0.1	5	1	11	19
181271	146.9	148.4			1.0	67	0.002	0.1	1	0.5	2	12
181272	148.4	149.9			1.0	67	0.002	0.1	9	0.5	1	12
181273	149.9	151.5			1.3	81	0.002	0.1	2	1	1	10
181274	151.5	154.5			1.2	40	0.007	0.1	1	0.5	0.5	9
181275	154.5	156.0			1.3	87	0.002	0.1	1	1	1	7
181276	156.0	157.6			1.2	75	0.002	0.1	2	0.5	1	7
181277	157.6	159.1			1.1	73	0.002	0.1	1	0.5	0.5	6

Assay Sample Log

LD06-32

Page: 4

Sample No.	From	To	Sample Type	S.G	Rec.	% Rec.	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
181278	159.1	160.6			0.8	53	0.002	0.1	1	0.5	1	7
181279	160.6	162.1			1.1	73	0.002	0.1	3	0.5	0.5	12
181280	162.1	163.7			0.9	56	0.002	0.1	1	0.5	1	5
181281	163.7	165.2			1.1	73	0.002	0.1	2	6	2	5
181282	165.2	166.7			1.0	67	0.002	0.2	2	2	1	6
181283	166.7	169.8			1.4	45	0.002	0.1	1	2	1	7
181284	169.8	172.8			1.1	37	0.008	0.2	3	5	1	8
181285	172.8	174.3			1.1	73	0.002	0.1	1	1	2	5
181286	174.3	175.9			1.1	69	0.002	0.1	1	1	1	4
181287	175.9	177.4			1.2	80	0.002	0.1	1	1	1	4
181288	177.4	178.9			1.4	93	0.002	0.2	1	2	1	4
181289	178.9	180.4			1.5	100	0.002	0.1	8	1	2	4
181290	180.4	182.0			1.4	88	0.002	0.1	8	1	3	7
181291	182.0	183.5			1.3	87	0.002	0.1	1	1	1	7
181292	183.5	185.0			1.4	93	0.002	0.1	1	1	1	7
181293	185.0	186.5			1.3	87	0.002	0.1	1	1	0.5	6
181294	186.5	188.1			1.4	88	0.002	0.2	1	1	1	6
181295	188.1	189.6			1.5	100	0.002	0.1	1	1	1	12
181296	189.6	191.1			1.4	93	0.002	0.1	1	5	1	8
181297	191.1	192.6			1.3	87	0.002	0.2	1	1	1	7
181298	192.6	194.1			1.3	87	0.002	0.2	1	1	2	10
181299	194.1	195.6			1.2	80	0.002	0.2	8	1	1	13
181300	195.6	197.2			1.2	75	0.002	0.2	1	1	1	11
181301	197.2	198.7			1.1	73	0.002	0.2	1	1	2	7
181302	198.7	200.2			0.9	60	0.002	0.2	4	1	2	10
181303	200.2	203.3			0.4	13	0.002	0.2	5	1	2	24
181304	203.3	204.8			1.1	73	0.002	0.2	1	0.5	1	11
181305	204.8	206.3			1.0	67	0.002	0.1	1	0.5	1	10
181306	206.3	207.8			1.1	73	0.002	0.1	1	1	2	9
181307	207.8	209.4			1.1	69	0.002	0.1	1	0.5	1	9
181308	209.4	210.9			1.0	67	0.002	0.2	2	0.5	1	8
181309	210.9	212.4			1.0	67	0.002	0.2	1	1	1	9
181310	212.4	213.9			1.0	67	0.002	0.2	11	1	1	7

RQD Log LD06-32

Date: Page:1

block	rqd (in)	RQD (cm)	RQD %	block	rqd (in)	RQD (cm)	RQD %
9.3				142.3			
11.3	15.5	39	20	145.4	72.5	184	59
14.3	58.0	147	49	148.4	47.5	121	40
17.4	8.0	20	7	151.5	34.5	88	28
20.4	57.5	146	49	154.5	15.0	38	13
23.5	53.0	135	43	157.5	56.5	144	48
26.5	36.5	93	31	160.6	21.5	55	18
29.6	32.0	81	26	163.7	18.0	46	15
32.6	17.0	43	14	166.7	12.0	30	10
35.7	20.0	51	16	169.8	5.0	13	4
38.7	11.0	28	9	172.8	0.0	0	0
41.8	14.0	36	11	175.9	13.5	34	11
44.8	28.0	71	24	178.9	16.0	41	14
47.9	38.0	97	31	182.0	41.5	105	34
50.9	0.0	0	0	185.0	26.0	66	22
53.9	39.0	99	33	188.1	42.0	107	34
57.0	32.5	83	27	191.1	52.0	132	44
60.0	55.0	140	47	194.1	37.0	94	31
63.1	46.0	117	38	197.2	13.0	33	11
66.1	0.0	0	0	200.2	30.0	76	25
69.2	64.5	164	53	203.3	0.0	0	0
72.2	49.5	126	42	206.3	4.0	10	3
75.3	7.0	18	6	209.4	8.0	20	7
78.3	39.5	100	33	212.4	10.5	27	9
81.4	33.5	85	27	215.5	0.0	0	0
84.4	67.0	170	57	218.8	5.0	13	4
87.5	52.5	133	43	221.6	52.5	133	48
90.5	42.0	107	36	224.6	12.0	30	10
93.6	62.0	157	51	227.7	12.0	30	10
96.6	54.0	137	46	230.7	4.0	10	3
99.7	38.0	97	31	233.8	4.0	10	3
102.7	74.0	188	63	236.8	0.0	0	0
105.8	52.0	132	43	239.9	13.0	33	11
108.8	68.5	174	58	242.9	12.0	30	10
111.9	58.5	149	48	246.0	31.0	79	25
114.9	37.0	94	31	249.0	51.0	130	43
118.0	5.5	14	5	252.1	76.0	193	62
121.0	56.5	144	48	255.1	74.0	188	63
124.0	75.5	192	64	258.2	72.5	184	59
127.1	79.0	201	65	261.2	18.0	46	15
130.1	59.0	150	50	264.2	33.0	84	28
133.2	28.0	71	23				
136.2	78.0	198	66			EOH @ 264.2m	
139.3	40.0	102	33				
142.3	51.0	130	43				

Appendix II

2006 Reverse Circulation Drill-hole Logs

Assay Sample Log LRC 06-01

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	160.0	no sample						
160.0	165.0	no sample						
165.0	170.0	no sample						
170.0	175.0	no sample						
175.0	180.0	no sample						
180.0	185.0	no sample						
185.0	190.0	no sample						
190.0	195.0	no sample						
195.0	200.0	no sample						
200.0	205.0	no sample						
205.0	210.0	no sample						
210.0	215.0	no sample						
215.0	220.0	no sample						
220.0	225.0	no sample						
225.0	230.0	no sample						
230.0	235.0	no sample						
235.0	240.0	no sample						
240.0	245.0	no sample						
245.0	250.0	no sample						
250.0	255.0	no sample						
255.0	260.0		<0.005	<0.2	11	25	2	113
260.0	265.0		0.01	<0.2	13	71	1	137
265.0	270.0		0.007	<0.2	6	33	1	130
270.0	275.0		<0.005	<0.2	9	30	1	102
275.0	280.0		<0.005	<0.2	11	44	<1	210
280.0	285.0		<0.005	<0.2	14	50	1	333
285.0	290.0		<0.005	<0.2	11	47	<1	160
290.0	295.0		0.007	<0.2	23	49	<1	259
295.0	300.0		0.006	<0.2	30	72	<1	897
300.0	305.0		0.006	<0.2	13	28	1	268
305.0	310.0		<0.005	0.2	28	62	<1	732
310.0	315.0		<0.005	<0.2	23	44	<1	259

Assay Sample Log LRC 06-01

page 2

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
315.0	320.0		0.005	<0.2	24	96	<1	396
320.0	325.0		<0.005	0.3	13	37	<1	132
325.0	330.0		<0.005	0.3	24	64	<1	229
330.0	335.0		<0.005	<0.2	14	43	<1	172
335.0	340.0		<0.005	<0.2	17	43	<1	264
340.0	345.0		0.006	<0.2	12	47	<1	98
345.0	350.0		<0.005	<0.2	6	51	<1	121
350.0	355.0		<0.005	<0.2	18	58	<1	250
355.0	360.0		<0.005	0.3	10	54	<1	134
360.0	365.0		<0.005	0.2	13	64	<1	123
365.0	370.0		<0.005	<0.2	4	38	<1	84
370.0	375.0		<0.005	<0.2	7	25	<1	105
375.0	380.0		<0.005	0.3	12	33	<1	104
380.0	385.0		<0.005	0.3	4	22	<1	69
385.0	390.0		<0.005	0.2	5	24	<1	83
390.0	395.0		<0.005	0.2	6	29	<1	117
395.0	400.0		<0.005	<0.2	12	39	<1	128
400.0	405.0		<0.005	0.4	14	39	<1	206
405.0	410.0		<0.005	0.2	13	44	<1	374
410.0	415.0		<0.005	0.2	10	70	<1	143
415.0	420.0		<0.005	0.3	19	44	<1	321
420.0	425.0		<0.005	0.5	17	55	<1	270
425.0	430.0		<0.005	0.3	21	91	<1	638
430.0	435.0		<0.005	0.2	17	61	<1	315
435.0	440.0		<0.005	0.2	23	68	<1	466
440.0	445.0		0.011	<0.2	11	66	<1	200
445.0	450.0		<0.005	0.2	15	39	<1	265
450.0	455.0		<0.005	0.2	21	53	<1	481
455.0	460.0		<0.005	0.4	26	74	<1	969
460.0	465.0		<0.005	0.3	25	94	<1	516
465.0	470.0		<0.005	0.3	24	84	<1	644
470.0	475.0		<0.005	0.4	14	33	<1	159
475.0	480.0		<0.005	0.3	15	49	<1	150

Assay Sample Log LRC 06-02

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	45.0	no sample						
45.0	50.0	no sample						
50.0	55.0	no sample						
55.0	60.0	no sample						
60.0	65.0	no sample						
65.0	70.0	no sample						
70.0	75.0	no sample						
75.0	80.0	no sample						
80.0	85.0	no sample						
85.0	90.0	no sample						
90.0	95.0	no sample						
95.0	100.0	no sample						
100.0	105.0	no sample						
105.0	110.0	no sample						
110.0	115.0	no sample						
115.0	120.0	no sample						
120.0	125.0	no sample						
125.0	130.0	no sample						
130.0	135.0	no sample						
135.0	140.0	no sample						
140.0	145.0	no sample						
145.0	150.0	no sample						
150.0	155.0	no sample						
155.0	160.0	no sample						
160.0	165.0	no sample						
165.0	170.0	no sample						
170.0	175.0	no sample						
175.0	180.0	no sample						
180.0	185.0	no sample						
185.0	190.0	no sample						
190.0	260.0	no sample						
260.0	265.0	no sample						

Assay Sample Log LRC 06-02

page 2

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
265.0	270.0	no sample						
270.0	275.0	no sample						
275.0	280.0		0.011	0.3	11	47	1	182
280.0	285.0		0.009	0.3	25	69	<1	426
285.0	290.0		0.008	0.5	32	79	<1	506
290.0	295.0		0.005	0.3	20	62	<1	787
295.0	300.0		0.01	0.3	44	96	<1	1570
300.0	305.0		0.007	<0.2	32	86	<1	1270
305.0	310.0		0.006	0.4	43	69	<1	996
310.0	315.0		0.007	<0.2	16	43	<1	397
315.0	320.0		<0.005	0.3	41	84	<1	1280
320.0	325.0		<0.005	0.2	11	40	<1	330
325.0	330.0		0.009	0.5	22	100	<1	492
330.0	335.0		<0.005	0.2	8	27	<1	248
335.0	340.0		<0.005	<0.2	6	23	<1	121
340.0	345.0		<0.005	<0.2	16	29	<1	268
345.0	350.0		<0.005	0.2	19	44	<1	456
350.0	355.0		<0.005	0.3	18	58	<1	801
355.0	360.0		<0.005	<0.2	9	42	<1	288
360.0	365.0		<0.005	0.3	15	87	<1	350
365.0	370.0		<0.005	0.2	21	70	<1	687
370.0	375.0		0.005	<0.2	11	34	<1	229
375.0	380.0		<0.005	0.2	16	66	<1	270
380.0	385.0		<0.005	0.3	12	52	1	250
385.0	390.0		0.007	<0.2	27	84	<1	670
390.0	395.0		<0.005	<0.2	26	81	<1	719
395.0	400.0		0.007	<0.2	30	73	<1	700
400.0	405.0		0.006	<0.2	31	85	<1	791
405.0	410.0		<0.005	0.2	11	157	<1	613
410.0	415.0		0.006	0.3	11	86	<1	245
415.0	420.0		0.005	0.5	11	95	<1	211
420.0	425.0		<0.005	0.2	18	78	<1	278
425.0	430.0		<0.005	<0.2	17	82	<1	420

Assay Sample Log LRC 06-04

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	20.0	no sample						
20.0	25.0		<0.005	<0.2	4	8	2	15
25.0	30.0		<0.005	<0.2	12	5	4	27
30.0	35.0		<0.005	<0.2	9	3	3	19
35.0	40.0		<0.005	0.2	9	5	3	14
40.0	45.0		<0.005	<0.2	3	1	1	8
45.0	50.0		<0.005	<0.2	10	5	2	21
50.0	55.0		<0.005	<0.2	9	5	2	26
55.0	60.0		<0.005	<0.2	10	6	2	27
60.0	65.0		<0.005	<0.2	22	14	3	50
65.0	70.0		<0.005	<0.2	9	5	2	29
70.0	75.0		<0.005	<0.2	5	2	1	12
75.0	80.0		<0.005	<0.2	5	3	2	20
80.0	85.0		<0.005	<0.2	4	2	2	18
85.0	90.0		<0.005	<0.2	2	1	1	9
90.0	95.0		<0.005	<0.2	9	3	2	20
95.0	100.0		<0.005	<0.2	8	3	2	16
100.0	105.0		<0.005	<0.2	9	2	2	19
105.0	110.0		<0.005	<0.2	5	2	2	14
110.0	115.0		0.045	<0.2	8	2	2	25
115.0	120.0		<0.005	<0.2	3	1	1	14
120.0	125.0		<0.005	<0.2	3	<1	1	17
125.0	130.0		<0.005	<0.2	3	<1	<1	10
130.0	135.0		<0.005	<0.2	<2	<1	1	9
135.0	140.0		<0.005	<0.2	7	2	1	17
140.0	145.0		<0.005	<0.2	3	<1	1	10
145.0	150.0		<0.005	<0.2	2	<1	1	12
150.0	155.0		<0.005	<0.2	3	<1	1	11
155.0	160.0		<0.005	<0.2	4	2	1	16
160.0	165.0		<0.005	<0.2	<2	<1	1	9
165.0	170.0		<0.005	<0.2	2	<1	<1	9
170.0	175.0		<0.005	<0.2	4	<1	<1	7

Assay Sample Log LRC 06-04

page 2

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
175.0	180.0		<0.005	<0.2	7	1	1	14
180.0	185.0		<0.005	0.2	7	<1	2	13
185.0	190.0		0.006	<0.2	56	5	7	50
190.0	195.0		0.012	<0.2	64	5	10	52
195.0	200.0		<0.005	0.2	35	3	6	31
200.0	205.0		<0.005	<0.2	21	3	4	35
205.0	210.0		<0.005	<0.2	18	2	4	19
210.0	215.0		<0.005	0.2	29	2	5	30
215.0	220.0		<0.005	<0.2	21	3	6	28
220.0	225.0		<0.005	<0.2	19	3	4	29
225.0	230.0		<0.005	0.2	13	2	3	20
230.0	235.0		<0.005	<0.2	17	1	3	18
235.0	240.0		<0.005	<0.2	16	1	4	14
240.0	245.0		0.005	<0.2	9	1	2	13
245.0	250.0		0.008	<0.2	34	2	9	34
250.0	255.0		<0.005	<0.2	12	1	2	15
255.0	260.0		0.005	<0.2	30	2	7	29
260.0	265.0		<0.005	<0.2	20	1	5	21
265.0	270.0		<0.005	<0.2	12	2	3	17
270.0	275.0		0.005	<0.2	16	1	4	20
275.0	280.0		<0.005	<0.2	8	1	3	12
280.0	285.0		<0.005	<0.2	8	5	1	22
285.0	290.0		<0.005	<0.2	6	3	2	18
290.0	295.0		<0.005	<0.2	12	4	2	20
295.0	300.0		0.009	<0.2	14	4	3	23
300.0	305.0		<0.005	<0.2	24	2	6	24
305.0	310.0		<0.005	<0.2	16	2	1	14
310.0	315.0		<0.005	<0.2	35	3	5	38
315.0	320.0		0.008	<0.2	24	2	2	17
320.0	325.0		0.005	<0.2	26	3	5	28
325.0	330.0		<0.005	<0.2	17	3	4	28
330.0	335.0		0.006	<0.2	10	2	3	23
335.0	340.0		<0.005	<0.2	16	2	2	24

Assay Sample Log LRC 06-05

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	20.0	no sample						
20.0	25.0		0.005	<0.2	41	7	5	31
25.0	30.0		<0.005	<0.2	11	3	2	10
30.0	35.0		<0.005	<0.2	11	1	2	7
35.0	40.0		<0.005	<0.2	8	2	1	6
40.0	45.0		0.006	<0.2	8	5	3	17
45.0	50.0		<0.005	<0.2	8	2	1	10
50.0	55.0		<0.005	<0.2	12	2	3	10
55.0	60.0		<0.005	<0.2	12	1	<1	8
60.0	65.0		<0.005	<0.2	5	<1	<1	6
65.0	70.0		<0.005	<0.2	10	3	<1	12
70.0	75.0		<0.005	<0.2	7	1	2	6
75.0	80.0		<0.005	<0.2	10	1	<1	6
80.0	85.0		<0.005	<0.2	<2	1	<1	5
85.0	90.0		<0.005	<0.2	5	1	3	7
90.0	95.0		<0.005	<0.2	7	1	2	9
95.0	100.0		<0.005	<0.2	7	<1	<1	8
100.0	105.0		<0.005	<0.2	<2	<1	3	6
105.0	110.0		<0.005	<0.2	2	1	1	7
110.0	115.0		<0.005	<0.2	6	1	2	8
115.0	120.0		<0.005	<0.2	15	5	5	18
120.0	125.0		<0.005	<0.2	11	5	6	18
125.0	130.0		<0.005	<0.2	<2	1	2	10
130.0	135.0	no sample						
135.0	140.0		<0.005	<0.2	8	1	1	9
140.0	145.0		<0.005	<0.2	<2	<1	<1	10
145.0	150.0		<0.005	<0.2	8	<1	<1	10
150.0	155.0		<0.005	<0.2	3	<1	<1	7
155.0	160.0		<0.005	<0.2	7	<1	4	34
160.0	165.0		<0.005	<0.2	5	<1	3	26
165.0	170.0		<0.005	<0.2	8	<1	1	15
170.0	175.0		<0.005	<0.2	11	<1	1	13

Assay Sample Log LRC 06-05

page 2

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
175.0	180.0		<0.005	<0.2	2	<1	1	12
180.0	185.0		<0.005	<0.2	6	2	1	15
185.0	190.0		<0.005	<0.2	7	2	1	13
190.0	195.0		<0.005	<0.2	6	3	2	16
195.0	200.0		<0.005	<0.2	<2	2	1	10
200.0	205.0		<0.005	<0.2	3	1	1	9
205.0	210.0		<0.005	<0.2	<2	2	1	10
210.0	215.0		<0.005	<0.2	4	1	1	9
215.0	220.0		<0.005	<0.2	2	1	<1	8
220.0	225.0		<0.005	<0.2	<2	2	1	8
225.0	230.0		<0.005	<0.2	<2	2	2	12
230.0	235.0		<0.005	<0.2	4	1	2	10
235.0	240.0		<0.005	<0.2	<2	1	1	9
240.0	245.0		<0.005	<0.2	<2	1	2	10
245.0	250.0		<0.005	<0.2	3	2	1	7
250.0	255.0		<0.005	<0.2	3	1	1	7
255.0	260.0		<0.005	<0.2	3	2	<1	7
260.0	265.0		<0.005	<0.2	<2	1	2	7
265.0	270.0		<0.005	<0.2	<2	1	1	8
270.0	275.0		<0.005	<0.2	2	1	2	16
275.0	280.0		<0.005	<0.2	6	1	3	13
280.0	285.0		0.005	<0.2	5	2	4	121
285.0	290.0		<0.005	<0.2	14	2	4	276
290.0	295.0		<0.005	<0.2	15	3	3	85
295.0	300.0		<0.005	<0.2	23	4	7	193
300.0	305.0		<0.005	<0.2	10	3	2	192
305.0	310.0		0.009	<0.2	54	9	<1	231
310.0	315.0		0.007	<0.2	26	9	1	233
315.0	320.0		0.017	<0.2	3	2	<1	12
320.0	325.0		<0.005	<0.2	<2	3	<1	10
325.0	330.0		<0.005	<0.2	2	2	1	21
330.0	335.0		<0.005	<0.2	14	3	<1	19
335.0	340.0		0.035	<0.2	63	9	3	97

Assay Sample Log LRC 06-06

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	80.0	no sample						
80.0	85.0		<0.005	<0.2	26	4	1	25
85.0	90.0	no sample						
90.0	95.0		0.014	<0.2	4	2	1	7
95.0	100.0		0.006	<0.2	4	<1	1	5
100.0	105.0		0.006	<0.2	6	<1	<1	5
105.0	110.0		<0.005	0.3	3	<1	<1	4
110.0	115.0		<0.005	<0.2	4	<1	1	6
115.0	120.0		<0.005	<0.2	2	<1	<1	4
120.0	125.0		<0.005	0.3	5	<1	<1	4
125.0	130.0		<0.005	<0.2	3	<1	1	9
130.0	135.0		<0.005	<0.2	6	<1	1	14
135.0	140.0		0.005	<0.2	6	1	1	19
140.0	145.0		0.005	<0.2	9	<1	1	21
145.0	150.0		0.006	<0.2	34	2	2	36
150.0	155.0		<0.005	<0.2	10	1	1	17
155.0	160.0		0.006	<0.2	4	2	1	13
160.0	165.0		<0.005	0.2	24	5	1	41
165.0	170.0		0.011	<0.2	19	11	2	34
170.0	175.0		0.007	0.8	21	40	3	88
175.0	180.0		0.008	<0.2	4	10	1	25
180.0	185.0		<0.005	<0.2	3	9	9	13
185.0	190.0		0.01	<0.2	4	7	5	18
190.0	195.0		<0.005	<0.2	10	10	2	12
195.0	200.0		0.01	<0.2	3	13	2	14
200.0	205.0		0.005	<0.2	5	52	1	19
205.0	210.0		<0.005	<0.2	<2	15	<1	19
210.0	215.0		<0.005	<0.2	5	35	1	27
215.0	220.0		<0.005	<0.2	2	19	1	22
220.0	225.0		<0.005	<0.2	8	18	3	27
225.0	230.0		<0.005	<0.2	3	35	3	27
230.0	235.0		0.006	<0.2	7	54	2	29

Assay Sample Log LRC 06-06

page 2

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
235.0	240.0		0.006	<0.2	7	54	2	29
240.0	245.0		0.007	<0.2	3	53	2	32
245.0	250.0		0.009	<0.2	<2	50	1	36
250.0	255.0		0.006	<0.2	3	34	5	34
255.0	260.0		<0.005	<0.2	22	25	2	35
260.0	265.0		0.007	<0.2	7	50	2	36
265.0	270.0		0.008	<0.2	6	36	1	28
270.0	275.0		<0.005	<0.2	4	40	1	31
275.0	280.0		0.005	<0.2	<2	18	1	25
280.0	285.0		0.008	<0.2	6	24	1	32
285.0	290.0		0.006	<0.2	4	36	1	35
290.0	295.0		0.006	<0.2	7	18	1	33
295.0	300.0		<0.005	<0.2	2	24	1	34
300.0	305.0		0.008	<0.2	7	24	1	28
305.0	310.0		<0.005	<0.2	4	17	1	28
310.0	315.0		<0.005	<0.2	6	52	<1	36
315.0	320.0		0.007	<0.2	3	46	1	27
320.0	325.0		0.005	<0.2	2	43	<1	31
325.0	330.0		<0.005	<0.2	<2	38	1	29
330.0	335.0		<0.005	<0.2	2	33	<1	28
335.0	340.0		<0.005	<0.2	3	53	1	30
340.0	345.0		<0.005	<0.2	2	17	<1	22
345.0	350.0		<0.005	<0.2	<2	44	1	22
350.0	355.0		0.007	<0.2	<2	60	1	29
355.0	360.0		0.006	<0.2	4	33	<1	28
360.0	365.0		<0.005	<0.2	3	55	1	31
365.0	370.0		<0.005	<0.2	3	34	1	48
370.0	375.0		0.007	<0.2	<2	68	<1	33
375.0	380.0		0.006	<0.2	2	79	1	36
380.0	385.0		0.019	<0.2	4	44	<1	27
385.0	390.0		0.058	<0.2	3	36	2	27
390.0	395.0		0.02	<0.2	2	179	<1	31
395.0	400.0		0.013	<0.2	<2	44	1	33

Diamond Drill Log

LRC06-07

Date:

Logged By: DJH

Page 1/ 2

From (ft)	To (ft)	Rock	Struct	@	CA	Alteration							Mineralization							Comments	
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG
0.0	110.0	OB																			Overburden
110.0	170.0	ATh																			Ash Tuff maroon, hematitic loc QZ veining? no visible mineralization
170.0	225.0	LS																			Limestone med grey no visible mineralization no QZ veining
225.0	245.0	ATh																			Ash Tuff a/a 110-170; maroon, hematitic loc QZ veining? no visible mineralization
245.0	255.0	ATs																			Ash Tuff pale beige, sericite? altered? no visible mineralization loc QZ veining?
255.0	290.0	ATh																			Ash Tuff a/a 110-170; maroon, hematitic no visible mineralization loc QZ veining?
290.0	295.0	ATs																			Ash Tuff a/a 245-255; pale beige, sericite? altered? w/ white QZ veining? no visible mineralization
295.0	340.0	ATh																			Ash Tuff a/a 110-170; maroon, hematitic native copper 315-325 w/ white QZ veining? no visible sulfide mineralization

Assay Sample Log LRC 06-07

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	110.0	no sample						
110.0	115.0		0.014	<0.2	<2	200	4	95
115.0	120.0		0.013	<0.2	7	242	11	87
120.0	125.0		0.015	<0.2	<2	226	3	97
125.0	130.0		0.017	<0.2	<2	297	2	103
130.0	135.0		0.015	<0.2	<2	408	1	104
135.0	140.0		0.014	<0.2	15	278	30	98
140.0	145.0		0.014	<0.2	<2	248	2	92
145.0	150.0		0.011	<0.2	<2	279	2	105
150.0	155.0		0.015	<0.2	<2	278	5	104
155.0	160.0		0.007	<0.2	3	216	2	109
160.0	165.0		0.013	<0.2	4	298	2	106
165.0	170.0		0.013	<0.2	<2	293	6	112
170.0	175.0		0.014	<0.2	8	348	38	124
175.0	180.0		0.011	0.7	13	340	7	108
180.0	185.0		<0.005	0.2	6	148	3	54
185.0	190.0		0.007	<0.2	7	197	9	72
190.0	195.0		<0.005	<0.2	7	121	3	44
195.0	200.0		<0.005	<0.2	<2	114	22	67
200.0	205.0		0.005	0.3	<2	104	30	48
205.0	210.0		<0.005	<0.2	<2	36	10	23
210.0	215.0		<0.005	<0.2	5	27	7	18
215.0	220.0		<0.005	<0.2	15	107	18	47
220.0	225.0		0.013	<0.2	<2	270	9	94
225.0	230.0		0.009	<0.2	<2	265	16	81
230.0	235.0		0.01	<0.2	6	221	40	89
235.0	240.0		0.015	<0.2	5	276	19	108
240.0	245.0		0.017	<0.2	<2	306	3	105
245.0	250.0		0.013	<0.2	<2	289	11	110
250.0	255.0		0.015	<0.2	5	305	39	103
255.0	260.0		0.01	<0.2	5	219	3	106
260.0	265.0		0.014	<0.2	2	336	2	124

Assay Sample Log LRC 06-07

page 2

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
265.0	270.0		0.013	<0.2	<2	242	1	111
270.0	275.0		0.012	<0.2	2	192	1	105
275.0	280.0		0.009	<0.2	<2	285	<1	120
280.0	285.0		0.01	<0.2	<2	299	1	115
285.0	290.0		0.008	0.2	2	347	1	114
290.0	295.0		0.011	<0.2	7	327	2	116
295.0	300.0		0.008	<0.2	<2	165	11	99
300.0	305.0		0.012	0.2	3	296	4	113
305.0	310.0		0.009	<0.2	<2	284	1	115
310.0	315.0		0.01	<0.2	5	262	2	108
315.0	320.0		0.006	0.6	3	4600	2	91
320.0	325.0		<0.005	0.2	<2	3650	<1	96
325.0	330.0		0.009	0.2	<2	1595	15	126
330.0	335.0		0.009	<0.2	5	350	33	95
335.0	340.0		0.011	<0.2	<2	538	<1	86
340.0	345.0		<0.005	0.2	4	1140	1	115
345.0	350.0		0.005	<0.2	6	559	<1	123
350.0	355.0		0.005	<0.2	<2	428	<1	115
355.0	360.0		0.006	<0.2	<2	385	<1	98
360.0	365.0		0.013	<0.2	<2	351	<1	126
365.0	370.0		0.012	<0.2	10	250	<1	108
370.0	375.0		0.009	<0.2	<2	200	<1	107
375.0	380.0		0.009	<0.2	30	204	50	96
380.0	385.0		0.011	<0.2	25	178	31	98
385.0	390.0		0.012	<0.2	3	134	10	127
390.0	395.0		0.013	<0.2	9	249	12	123
395.0	400.0		0.015	<0.2	9	322	2	125
400.0	405.0		0.013	<0.2	11	310	<1	119
405.0	410.0		0.014	<0.2	<2	239	<1	114
410.0	415.0		0.012	<0.2	11	149	9	104
415.0	420.0		0.013	<0.2	8	435	61	123
420.0	425.0		0.007	0.2	9	317	42	114
425.0	430.0		0.013	<0.2	5	310	14	120

Assay Sample Log LRC 06-08

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	155.0	no sample						
155.0	160.0		<0.005	<0.2	10	208	4	124
160.0	165.0		<0.005	<0.2	4	206	4	87
165.0	170.0		<0.005	<0.2	5	130	<1	73
170.0	175.0		<0.005	<0.2	4	160	5	90
175.0	180.0		0.009	<0.2	4	201	<1	104
180.0	185.0		<0.005	<0.2	<2	361	1	78
185.0	190.0		<0.005	<0.2	2	230	<1	74
190.0	195.0		0.005	<0.2	7	207	<1	95
195.0	200.0		0.005	<0.2	2	292	<1	124
200.0	205.0		<0.005	<0.2	3	199	<1	114
205.0	210.0		<0.005	<0.2	2	258	<1	131
210.0	215.0		<0.005	<0.2	4	217	<1	119
215.0	220.0		0.005	<0.2	<2	140	<1	130
220.0	225.0		<0.005	<0.2	4	126	<1	119
225.0	230.0		<0.005	<0.2	<2	150	<1	128
230.0	235.0		<0.005	<0.2	5	219	2	118
235.0	240.0		<0.005	0.3	3	200	5	93
240.0	245.0		<0.005	<0.2	2	363	5	96
245.0	250.0		<0.005	0.2	14	382	13	97
250.0	255.0		<0.005	0.2	298	468	87	114
255.0	260.0		0.141	<0.2	1390	214	25	105
260.0	265.0		0.192	<0.2	2250	195	19	117
265.0	270.0		0.047	<0.2	1230	120	10	110
270.0	275.0		0.035	<0.2	1100	510	98	117
275.0	280.0		0.018	<0.2	454	74	9	40
280.0	285.0		0.009	<0.2	273	48	5	32
285.0	290.0		<0.005	0.2	59	21	3	16
290.0	295.0		<0.005	<0.2	24	11	<1	12
295.0	300.0		<0.005	0.2	31	24	2	23
300.0	305.0		<0.005	<0.2	20	9	1	12
305.0	310.0		<0.005	0.2	17	32	5	11

Assay Sample Log LRC 06-08

page 2

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
310.0	315.0		<0.005	<0.2	10	7	1	11
315.0	320.0		<0.005	<0.2	11	10	1	9
320.0	325.0		<0.005	<0.2	8	5	1	9
325.0	330.0		<0.005	0.2	23	15	2	15
330.0	335.0		<0.005	<0.2	15	6	1	15
335.0	340.0		<0.005	<0.2	11	5	1	13
340.0	345.0		<0.005	<0.2	5	5	1	15
345.0	350.0		<0.005	<0.2	8	5	1	18
350.0	355.0		<0.005	<0.2	7	6	2	18
355.0	360.0		<0.005	0.2	4	3	1	28
360.0	365.0		<0.005	0.2	<2	5	2	13
365.0	370.0		<0.005	0.2	23	6	2	7
370.0	375.0		<0.005	0.3	<2	3	1	6
375.0	380.0		<0.005	0.2	4	2	<1	5
380.0	385.0		<0.005	0.3	<2	3	2	7
385.0	390.0		<0.005	0.3	21	8	2	15
390.0	395.0		<0.005	<0.2	2	3	1	14
395.0	400.0		<0.005	<0.2	<2	2	1	16
400.0	405.0		<0.005	0.2	3	4	2	17
405.0	410.0		<0.005	<0.2	10	2	<1	33
410.0	415.0		<0.005	<0.2	<2	2	<1	17
415.0	420.0		<0.005	0.2	3	2	<1	17
420.0	425.0		<0.005	0.4	8	10	1	36
425.0	430.0		<0.005	0.5	62	36	3	38
430.0	435.0		<0.005	0.3	7	8	<1	25
435.0	440.0		<0.005	0.2	2	6	<1	17
440.0	445.0		<0.005	0.2	6	4	<1	20
445.0	450.0		<0.005	<0.2	7	6	<1	28
450.0	455.0		<0.005	<0.2	<2	6	<1	23
455.0	460.0		<0.005	<0.2	<2	5	<1	16
460.0	465.0		<0.005	<0.2	<2	3	<1	14
465.0	470.0		<0.005	<0.2	14	5	<1	26
470.0	475.0		<0.005	0.2	9	2	<1	23

Assay Sample Log LRC 06-09

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	20.0	no sample						
20.0	25.0		<0.005	0.2	97	13	8	66
25.0	30.0		<0.005	0.2	62	8	6	44
30.0	35.0		<0.005	<0.2	27	4	2	15
35.0	40.0		<0.005	<0.2	57	3	1	16
40.0	45.0		<0.005	<0.2	16	2	<1	15
45.0	50.0		<0.005	<0.2	342	5	2	23
50.0	55.0		0.005	0.5	5050	29	28	65
55.0	60.0		0.006	0.3	2910	18	17	81
60.0	65.0		<0.005	0.2	1105	6	5	100
65.0	70.0		<0.005	0.3	1505	10	8	91
70.0	75.0		<0.005	0.2	589	10	5	74
75.0	80.0		<0.005	<0.2	105	5	2	65
80.0	85.0		<0.005	<0.2	694	6	6	73
85.0	90.0		<0.005	<0.2	433	6	4	41
90.0	95.0		<0.005	0.2	86	3	1	23
95.0	100.0		<0.005	<0.2	186	4	2	28
100.0	105.0		<0.005	0.2	36	3	6	29
105.0	110.0		<0.005	0.2	26	3	7	36
110.0	115.0		<0.005	0.2	46	5	9	53
115.0	120.0		<0.005	0.2	16	3	4	25
120.0	125.0		<0.005	0.2	45	4	2	45
125.0	130.0		<0.005	<0.2	36	4	3	34
130.0	135.0		<0.005	0.2	10	3	1	16
135.0	140.0		<0.005	0.2	24	4	2	27
140.0	145.0		<0.005	0.2	37	6	2	34
145.0	150.0		<0.005	0.2	31	5	2	37
150.0	155.0		<0.005	<0.2	35	3	3	25
155.0	160.0		<0.005	0.2	81	4	3	27
160.0	165.0		<0.005	0.2	96	3	1	24
165.0	170.0		<0.005	0.2	82	4	3	35
170.0	175.0		<0.005	<0.2	157	3	3	24

Assay Sample Log LRC 06-10

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	20.0	no sample						
20.0	25.0		<0.005	<0.2	5	2	2	10
25.0	30.0		0.005	<0.2	<2	1	2	10
30.0	35.0		0.005	<0.2	8	2	4	13
35.0	40.0		0.009	<0.2	5	1	3	8
40.0	45.0		<0.005	<0.2	17	3	20	28
45.0	50.0		<0.005	<0.2	40	6	29	64
50.0	55.0		<0.005	<0.2	40	9	23	90
55.0	60.0		<0.005	<0.2	21	6	14	49
60.0	65.0		0.006	0.5	111	36	21	173
65.0	70.0		0.009	0.2	95	33	19	124
70.0	75.0		0.007	<0.2	61	23	15	74
75.0	80.0		<0.005	<0.2	15	5	8	23
80.0	85.0		<0.005	<0.2	37	15	14	48
85.0	90.0		0.005	<0.2	44	18	11	57
90.0	95.0		<0.005	<0.2	4	1	2	10
95.0	100.0		<0.005	<0.2	4	1	2	11
100.0	105.0		0.012	<0.2	17	3	7	23
105.0	110.0		<0.005	<0.2	7	2	2	8
110.0	115.0		0.005	<0.2	25	5	7	24
115.0	120.0		<0.005	<0.2	23	4	8	23
120.0	125.0		<0.005	<0.2	21	4	6	21
125.0	130.0		<0.005	<0.2	11	2	4	10
130.0	135.0		<0.005	<0.2	10	2	5	11
135.0	140.0		<0.005	<0.2	8	6	3	19
140.0	145.0		<0.005	<0.2	10	3	6	14
145.0	150.0		<0.005	<0.2	9	2	6	16
150.0	155.0		<0.005	<0.2	67	6	15	44
155.0	160.0		0.007	<0.2	200	23	38	180
160.0	165.0		0.005	<0.2	27	3	6	25
165.0	170.0		0.01	<0.2	19	3	6	23
170.0	175.0		<0.005	<0.2	22	3	6	24

Assay Sample Log LRC 06-11

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	25.0	no sample						
25.0	30.0		<0.005	<0.2	19	6	7	40
30.0	35.0		<0.005	<0.2	16	6	5	37
35.0	40.0		<0.005	<0.2	24	8	6	42
40.0	45.0		<0.005	<0.2	29	8	6	48
45.0	50.0		<0.005	<0.2	27	5	7	43
50.0	55.0		<0.005	<0.2	18	4	5	40
55.0	60.0		<0.005	<0.2	10	2	3	27
60.0	65.0		<0.005	<0.2	18	4	4	38
65.0	70.0		<0.005	<0.2	16	4	5	34
70.0	75.0		<0.005	<0.2	20	5	5	43
75.0	80.0		<0.005	<0.2	17	3	4	32
80.0	85.0		<0.005	<0.2	21	3	4	33
85.0	90.0		<0.005	<0.2	23	3	3	23
90.0	95.0		<0.005	<0.2	28	3	6	31
95.0	100.0		<0.005	<0.2	47	4	12	44
100.0	105.0		<0.005	<0.2	24	2	9	30
105.0	110.0		<0.005	<0.2	17	2	5	25
110.0	115.0		<0.005	<0.2	13	2	3	22
115.0	120.0		<0.005	<0.2	19	2	4	22
120.0	125.0		<0.005	<0.2	15	3	4	29
125.0	130.0		<0.005	<0.2	14	2	6	21
130.0	135.0		0.015	<0.2	12	6	9	73
135.0	140.0		0.02	0.4	84	42	17	412
140.0	145.0		0.005	0.2	31	18	20	162
145.0	150.0		<0.005	<0.2	11	4	6	44
150.0	155.0		<0.005	<0.2	13	4	3	53
155.0	160.0		<0.005	<0.2	12	2	2	23
160.0	165.0		<0.005	<0.2	102	7	25	74
165.0	170.0		0.005	<0.2	46	4	4	43
170.0	175.0		<0.005	0.2	13	4	5	26
175.0	180.0		<0.005	<0.2	8	3	3	23

Diamond Drill Log

LRC06-12

Date:

Logged By: DJH

Page 1 / 2

From (ft)	To (ft)	Rock	Struct	@	CA	Alteration							Mineralization							Comments				
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG			
0.0	55.0	OB																						Overburden
55.0	175.0	LS																						Limestone white/med grey loc orange oxide?/carbonate?
175.0	190.0	LS-A																						Limestone and Argillite Intermixed cnt between med grey/white limestone and black argillite w/ QZ veining 180-185
190.0	205.0	A									tr													Argillite black PY as disseminated grains
205.0	220.0	Fd-A																						Felsite Dyke and Argillite Mixed Interval It creamy/beige felsite and black argillite no visible mineralization wkly calcareous
220.0	305.0	A									tr													Argillite black PY as disseminated grains
305.0	310.0	Fd									tr													Felsite Dyke? It creamy/beige w/ 5% black argillite wkly calcareous PY as fine disseminations in argillite
310.0	320.0	A									tr													Argillite black w/ <5% creamy/beige felsite PY as fine disseminations in argillite
320.0	325.0	Fd																						Felsite Dyke It creamy/beige felsite w/ <10% black argillite no visible mineralization

Assay Sample Log LRC 06-12

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	55.0	no sample						
55.0	60.0		<0.005	<0.2	11	1	5	23
60.0	65.0		<0.005	<0.2	26	3	7	36
65.0	70.0		<0.005	<0.2	9	3	4	18
70.0	75.0		<0.005	<0.2	8	2	3	26
75.0	80.0		<0.005	<0.2	10	1	3	22
80.0	85.0		<0.005	<0.2	3	<1	<1	10
85.0	90.0		<0.005	<0.2	10	15	1	7
90.0	95.0		<0.005	<0.2	5	13	2	8
95.0	100.0		<0.005	<0.2	15	1	3	18
100.0	105.0		0.005	<0.2	16	4	5	38
105.0	110.0		0.006	<0.2	21	2	8	27
110.0	115.0		<0.005	<0.2	6	1	2	21
115.0	120.0		<0.005	<0.2	9	1	2	19
120.0	125.0		<0.005	<0.2	5	<1	1	13
125.0	130.0		<0.005	<0.2	3	<1	<1	11
130.0	135.0		<0.005	<0.2	3	<1	3	8
135.0	140.0		<0.005	<0.2	8	1	1	18
140.0	145.0		<0.005	<0.2	9	<1	1	23
145.0	150.0		<0.005	<0.2	12	2	2	20
150.0	155.0		<0.005	<0.2	7	1	<1	17
155.0	160.0		<0.005	<0.2	3	<1	1	7
160.0	165.0		<0.005	<0.2	9	<1	<1	9
165.0	170.0		<0.005	<0.2	<2	<1	1	16
170.0	175.0		<0.005	<0.2	5	1	1	17
175.0	180.0		0.005	0.2	35	26	8	35
180.0	185.0		<0.005	<0.2	22	33	6	39
185.0	190.0		<0.005	0.6	10	60	1	123
190.0	195.0		0.005	<0.2	26	59	1	258
195.0	200.0		<0.005	0.5	22	61	<1	201
200.0	205.0		<0.005	<0.2	18	66	1	205
205.0	210.0		<0.005	0.3	26	80	1	247

Assay Sample Log LRC 06-12

page 2

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
210.0	215.0		<0.005	0.5	16	99	<1	146
215.0	220.0		<0.005	0.4	11	91	1	85
220.0	225.0		<0.005	0.6	16	80	<1	158
225.0	230.0		<0.005	0.4	20	77	1	299
230.0	235.0		<0.005	0.5	21	75	<1	293
235.0	240.0		<0.005	0.2	21	56	<1	288
240.0	245.0		<0.005	0.3	26	78	<1	264
245.0	250.0		<0.005	<0.2	15	49	<1	136
250.0	255.0		<0.005	0.3	18	84	<1	265
255.0	260.0		<0.005	0.3	9	48	<1	103
260.0	265.0		<0.005	0.3	15	58	<1	162
265.0	270.0		<0.005	0.2	19	66	1	357
270.0	275.0		<0.005	0.3	21	79	2	390
275.0	280.0		<0.005	0.3	25	83	1	634
280.0	285.0		0.009	0.3	19	75	<1	409
285.0	290.0		<0.005	0.2	17	67	1	252
290.0	295.0		0.007	0.2	21	75	<1	244
295.0	300.0		<0.005	<0.2	13	56	<1	151
300.0	305.0		<0.005	0.3	12	61	<1	292
305.0	310.0		<0.005	<0.2	8	22	<1	119
310.0	315.0		<0.005	0.2	7	52	<1	231
315.0	320.0		<0.005	0.3	21	66	<1	268
320.0	325.0		<0.005	0.4	12	45	1	185
325.0	330.0		<0.005	0.3	21	78	1	314
330.0	335.0		<0.005	0.4	19	81	<1	473
335.0	340.0		<0.005	0.2	9	63	2	283
340.0	345.0		<0.005	<0.2	9	39	<1	107
345.0	350.0		0.005	0.2	12	53	<1	225
350.0	355.0		<0.005	0.2	21	71	<1	327
355.0	360.0		0.006	0.2	20	87	<1	307
360.0	365.0		<0.005	0.3	22	89	1	472
365.0	370.0		0.005	0.3	21	80	<1	449
370.0	375.0		0.006	0.3	20	92	<1	446

Assay Sample Log LRC 06-13

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	60.0	no sample						
60.0	65.0		<0.005	<0.2	5	21	<1	8
65.0	70.0		<0.005	<0.2	3	2	1	10
70.0	75.0		<0.005	<0.2	4	6	2	22
75.0	80.0		<0.005	<0.2	3	9	1	9
80.0	85.0		<0.005	0.2	<2	12	1	11
85.0	90.0		<0.005	<0.2	5	3	1	12
90.0	95.0		<0.005	0.3	<2	3	1	8
95.0	100.0		0.005	<0.2	3	3	1	9
100.0	105.0		<0.005	<0.2	<2	2	1	8
105.0	110.0		<0.005	<0.2	<2	2	1	7
110.0	115.0		<0.005	<0.2	<2	2	1	7
115.0	120.0		<0.005	<0.2	3	4	1	9
120.0	125.0		<0.005	<0.2	4	4	1	11
125.0	130.0		<0.005	<0.2	2	3	1	14
130.0	135.0		<0.005	0.2	<2	3	1	6
135.0	140.0		<0.005	0.2	<2	6	1	8
140.0	145.0		<0.005	<0.2	<2	5	1	8
145.0	150.0		<0.005	<0.2	<2	3	<1	12
150.0	155.0		<0.005	<0.2	2	3	<1	11
155.0	160.0		<0.005	<0.2	3	2	<1	11
160.0	165.0		<0.005	<0.2	4	2	1	14
165.0	170.0		<0.005	<0.2	3	2	1	5
170.0	175.0		<0.005	<0.2	<2	2	1	9
175.0	180.0		<0.005	<0.2	2	5	1	11
180.0	185.0		<0.005	<0.2	<2	2	<1	10
185.0	190.0		<0.005	<0.2	<2	3	1	12
190.0	195.0		<0.005	<0.2	2	2	4	11
195.0	200.0		<0.005	<0.2	2	3	1	12
200.0	205.0		<0.005	<0.2	3	3	1	7
205.0	210.0		<0.005	<0.2	2	5	8	19
210.0	215.0		0.005	<0.2	4	6	6	22

Assay Sample Log LRC 06-13

page 2

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
215.0	220.0		<0.005	<0.2	<2	4	3	13
220.0	225.0		<0.005	<0.2	<2	3	1	10
225.0	230.0		<0.005	<0.2	4	3	3	19
230.0	235.0		<0.005	<0.2	<2	4	2	16
235.0	240.0		<0.005	<0.2	4	6	2	24
240.0	245.0		<0.005	<0.2	6	5	6	13
245.0	250.0		<0.005	<0.2	2	5	3	14
250.0	255.0		<0.005	<0.2	5	3	4	10
255.0	260.0		<0.005	<0.2	<2	4	12	11
260.0	265.0		<0.005	<0.2	<2	4	29	9
265.0	270.0		<0.005	<0.2	3	4	10	12
270.0	275.0		<0.005	<0.2	<2	5	3	24
275.0	280.0		<0.005	<0.2	7	6	16	13
280.0	285.0		<0.005	<0.2	6	6	8	18
285.0	290.0		<0.005	<0.2	9	5	16	11
290.0	295.0		<0.005	<0.2	4	5	5	9
295.0	300.0		<0.005	<0.2	2	4	4	16
300.0	305.0		<0.005	<0.2	<2	6	4	17
305.0	310.0		<0.005	<0.2	4	8	2	20
310.0	315.0		<0.005	<0.2	4	8	4	30
315.0	320.0		<0.005	<0.2	<2	3	2	29
320.0	325.0		<0.005	<0.2	<2	5	2	17
325.0	330.0		<0.005	<0.2	4	2	5	9
330.0	335.0		<0.005	<0.2	<2	2	1	6
335.0	340.0		<0.005	<0.2	<2	3	2	8
340.0	345.0		<0.005	<0.2	<2	3	2	25
345.0	350.0		<0.005	<0.2	5	3	1	10
350.0	355.0		<0.005	<0.2	<2	2	<1	10
355.0	360.0		<0.005	<0.2	2	2	1	8
360.0	365.0		<0.005	<0.2	3	1	1	6
365.0	370.0		<0.005	<0.2	<2	2	1	5
370.0	375.0		<0.005	<0.2	2	2	1	5
375.0	380.0		<0.005	<0.2	2	8	2	24

Assay Sample Log LRC 06-14

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	30.0	no sample						
30.0	35.0		0.007	0.2	4	76	<1	86
35.0	40.0		<0.005	0.2	5	62	<1	71
40.0	45.0		<0.005	<0.2	5	67	1	77
45.0	50.0		<0.005	<0.2	3	65	<1	79
50.0	55.0		<0.005	<0.2	5	62	<1	75
55.0	60.0		<0.005	<0.2	3	53	<1	61
60.0	65.0		0.011	0.2	3	60	<1	69
65.0	70.0		<0.005	0.2	3	60	<1	67
70.0	75.0		<0.005	<0.2	3	59	<1	60
75.0	80.0		0.006	<0.2	4	67	<1	76
80.0	85.0		<0.005	<0.2	3	56	<1	61
85.0	90.0		<0.005	<0.2	6	64	<1	74
90.0	95.0		<0.005	<0.2	5	55	<1	64
95.0	100.0		<0.005	<0.2	5	53	<1	64
100.0	105.0		<0.005	0.2	3	61	1	73
105.0	110.0		<0.005	0.2	8	64	<1	78
110.0	115.0		0.005	0.3	11	72	<1	93
115.0	120.0		<0.005	0.2	9	62	<1	80
120.0	125.0		<0.005	0.3	6	76	<1	93
125.0	130.0		<0.005	0.4	7	71	<1	86
130.0	135.0		<0.005	<0.2	5	70	<1	90
135.0	140.0		0.005	<0.2	9	69	<1	87
140.0	145.0		<0.005	0.2	4	72	<1	87
145.0	150.0		<0.005	<0.2	7	66	<1	84
150.0	155.0		<0.005	0.3	4	66	<1	85
155.0	160.0		<0.005	0.4	4	73	<1	91
160.0	165.0		<0.005	<0.2	3	65	<1	85
165.0	170.0		0.009	0.2	7	69	<1	95
170.0	175.0		<0.005	<0.2	6	70	<1	91
175.0	180.0		<0.005	<0.2	2	44	<1	55
180.0	185.0		<0.005	0.2	7	59	<1	73

Assay Sample Log LRC 06-14

page 2

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
185.0	190.0		<0.005	<0.2	5	62	<1	74
190.0	195.0		<0.005	0.2	5	59	<1	72
195.0	200.0		<0.005	0.2	2	58	<1	69
200.0	205.0		<0.005	0.4	3	72	1	97
205.0	210.0		<0.005	<0.2	6	72	1	93
210.0	215.0		0.005	<0.2	6	72	<1	93
215.0	220.0		<0.005	0.2	7	63	<1	83
220.0	225.0		<0.005	<0.2	6	59	<1	76
225.0	230.0		<0.005	0.3	4	62	<1	75
230.0	235.0		<0.005	<0.2	5	56	<1	65
235.0	240.0		<0.005	0.2	5	58	<1	79
240.0	245.0		<0.005	0.2	3	62	<1	74
245.0	250.0		<0.005	<0.2	6	60	<1	73
250.0	255.0		<0.005	<0.2	4	47	<1	60
255.0	260.0		<0.005	<0.2	6	65	<1	71
260.0	265.0		<0.005	<0.2	8	70	<1	83
265.0	270.0		<0.005	<0.2	<2	68	<1	77
270.0	275.0		<0.005	0.2	8	68	<1	81
275.0	280.0		<0.005	<0.2	8	50	1	60
280.0	285.0		<0.005	<0.2	3	67	1	68
285.0	290.0		<0.005	0.2	<2	67	1	76
290.0	295.0		<0.005	<0.2	6	73	2	92
295.0	300.0		<0.005	0.2	2	61	1	65
300.0	305.0		<0.005	<0.2	7	64	1	67
305.0	310.0		<0.005	<0.2	3	63	1	58
310.0	315.0		<0.005	<0.2	6	44	1	48
315.0	320.0		<0.005	<0.2	<2	50	1	64
320.0	325.0		0.016	<0.2	7	43	1	65
325.0	330.0		<0.005	<0.2	5	41	1	68
330.0	335.0		<0.005	<0.2	4	61	1	79
335.0	340.0		<0.005	<0.2	8	60	1	80
340.0	345.0		<0.005	0.2	6	58	1	91
345.0	350.0		<0.005	0.2	24	67	1	105

Diamond Drill Log

LRC06-15

Date:

Logged By: DJH

Page 1/2

From (ft)	To (ft)	Rock	Struct	@	CA	Alteration								Mineralization								Comments
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN	MG		
0.0	15.0	OB																				Overburden
15.0	115.0	LS																				Limestone med grey no visible mineralization
115.0	120.0	A									tr											Argillite black PY as disseminated grains
120.0	150.0	ATc									tr											Ash Tuff It green, chloritic, foliated (flat chips) loc argillaceous PY in <vnlt
150.0	190.0	A									tr											Argillite black PY as disseminated grains
190.0	250.0	LSt									tr											Tuffaceous Limestone grey/green, chloritic possible mafic tuff PY in <vnlt
250.0	290.0	Ca									tr											Argillaceous Chert It green/grey, loc dk grey PY in <vnlt
290.0	370.0	A									tr											Argillite black, loc tuffaceous PY in <vnlt, vnlt
370.0	465.0	ATc																				Chloritic Ash Tuff It green; loc argillaceous no visible mineralization

Assay Sample Log LRC 06-15

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	15.0	no sample						
15.0	20.0		<0.005	<0.2	8	27	<1	55
20.0	25.0		<0.005	<0.2	10	26	<1	65
25.0	30.0		<0.005	<0.2	9	21	<1	56
30.0	35.0		<0.005	<0.2	8	18	<1	44
35.0	40.0		<0.005	<0.2	7	13	<1	36
40.0	45.0		<0.005	<0.2	3	7	<1	19
45.0	50.0		<0.005	<0.2	<2	5	<1	31
50.0	55.0		<0.005	<0.2	5	5	<1	19
55.0	60.0		<0.005	<0.2	5	6	<1	21
60.0	65.0		<0.005	<0.2	2	4	<1	16
65.0	70.0		<0.005	<0.2	<2	3	<1	18
70.0	75.0		<0.005	<0.2	2	5	<1	17
75.0	80.0		<0.005	<0.2	3	7	<1	23
80.0	85.0		<0.005	<0.2	<2	13	<1	38
85.0	90.0		<0.005	<0.2	<2	15	<1	37
90.0	95.0		<0.005	<0.2	2	14	<1	34
95.0	100.0		<0.005	<0.2	3	20	<1	45
100.0	105.0		<0.005	<0.2	4	20	<1	43
105.0	110.0		<0.005	<0.2	7	13	<1	30
110.0	115.0		<0.005	<0.2	32	15	<1	36
115.0	120.0		<0.005	<0.2	34	16	<1	36
120.0	125.0		<0.005	<0.2	6	43	1	50
125.0	130.0		<0.005	0.2	4	95	<1	70
130.0	135.0		<0.005	<0.2	<2	256	<1	64
135.0	140.0		<0.005	<0.2	<2	136	<1	55
140.0	145.0		<0.005	<0.2	2	138	<1	59
145.0	150.0		<0.005	<0.2	7	138	<1	63
150.0	155.0		<0.005	0.3	3	94	<1	67
155.0	160.0		0.006	0.8	8	80	<1	98
160.0	165.0		0.006	0.6	7	62	<1	71
165.0	170.0		0.008	0.7	3	49	<1	60

Assay Sample Log LRC 06-15

page 2

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
170.0	175.0		0.007	1	3	57	<1	75
175.0	180.0		<0.005	0.4	5	54	<1	97
180.0	185.0		<0.005	0.7	8	59	<1	170
185.0	190.0		<0.005	0.3	5	59	<1	70
190.0	195.0		<0.005	0.3	4	89	<1	108
195.0	200.0		<0.005	<0.2	3	94	<1	107
200.0	205.0		<0.005	0.2	4	84	<1	116
205.0	210.0		<0.005	0.4	<2	81	<1	94
210.0	215.0		<0.005	<0.2	<2	51	<1	59
215.0	220.0		0.01	0.4	3	117	<1	103
220.0	225.0		<0.005	0.5	2	132	<1	84
225.0	230.0		0.027	0.3	3	114	1	71
230.0	235.0		<0.005	<0.2	2	60	<1	41
235.0	240.0		<0.005	<0.2	5	58	<1	45
240.0	245.0		<0.005	<0.2	3	75	<1	50
245.0	250.0		<0.005	<0.2	<2	42	<1	45
250.0	255.0		<0.005	0.2	3	74	<1	55
255.0	260.0		<0.005	<0.2	4	112	<1	37
260.0	265.0		<0.005	<0.2	<2	113	<1	37
265.0	270.0		<0.005	<0.2	3	109	<1	39
270.0	275.0		<0.005	<0.2	<2	103	<1	37
275.0	280.0		<0.005	<0.2	5	108	<1	61
280.0	285.0		<0.005	0.2	4	99	1	108
285.0	290.0		<0.005	0.3	4	89	<1	100
290.0	295.0		<0.005	0.3	4	49	<1	86
295.0	300.0		0.006	0.3	3	66	<1	73
300.0	305.0		0.009	0.4	6	82	<1	79
305.0	310.0		0.007	0.3	4	87	<1	86
310.0	315.0		0.006	0.3	3	80	1	82
315.0	320.0		0.026	0.3	2	93	<1	83
320.0	325.0		<0.005	0.3	4	130	<1	89
325.0	330.0		0.008	0.2	5	93	1	85
330.0	335.0		0.011	<0.2	5	106	1	91

Assay Sample Log LRC 06-15

page 4

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
141.7	152.4	10.7 m					93	

Assay Sample Log LRC 06-16

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	35.0	no sample						
35.0	40.0		<0.005	<0.2	8	3	4	19
40.0	45.0		<0.005	<0.2	12	1	2	17
45.0	50.0		<0.005	<0.2	3	<1	1	14
50.0	55.0		<0.005	<0.2	5	<1	3	14
55.0	60.0		<0.005	<0.2	6	<1	4	14
60.0	65.0		0.008	<0.2	35	12	14	50
65.0	70.0		0.006	<0.2	21	7	16	37
70.0	75.0		<0.005	<0.2	10	1	4	14
75.0	80.0		<0.005	<0.2	34	8	12	57
80.0	85.0		<0.005	0.3	37	10	10	54
85.0	90.0		0.006	0.2	61	24	74	99
90.0	95.0		<0.005	<0.2	13	3	10	23
95.0	100.0		0.005	<0.2	18	8	13	49
100.0	105.0		<0.005	<0.2	21	8	22	37
105.0	110.0		<0.005	<0.2	13	6	13	29
110.0	115.0		<0.005	<0.2	8	3	8	21
115.0	120.0		<0.005	<0.2	11	3	8	32
120.0	125.0		<0.005	<0.2	12	4	10	118
125.0	130.0		0.009	<0.2	12	3	21	80
130.0	135.0		<0.005	<0.2	3	2	3	26
135.0	140.0		<0.005	<0.2	13	5	13	31
140.0	145.0		<0.005	<0.2	11	5	9	27
145.0	150.0		<0.005	<0.2	4	4	7	24
150.0	155.0		<0.005	<0.2	11	4	5	24
155.0	160.0		<0.005	<0.2	2	2	3	19
160.0	165.0		<0.005	<0.2	10	4	14	28
165.0	170.0		<0.005	<0.2	12	4	15	33
170.0	175.0		<0.005	<0.2	14	5	13	32
175.0	180.0		<0.005	<0.2	6	2	4	18
180.0	185.0		<0.005	<0.2	5	2	3	16
185.0	190.0		<0.005	<0.2	5	2	3	19

Assay Sample Log LRC 06-16

page 2

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
190.0	195.0		<0.005	<0.2	4	2	6	25
195.0	200.0		<0.005	<0.2	10	3	15	61
200.0	205.0		<0.005	<0.2	6	3	20	61
205.0	210.0		<0.005	<0.2	13	3	10	32
210.0	215.0		<0.005	<0.2	14	4	9	34
215.0	220.0		<0.005	<0.2	8	3	5	23
220.0	225.0		<0.005	<0.2	5	2	4	19
225.0	230.0		<0.005	<0.2	2	1	3	14
230.0	235.0		0.11	<0.2	2	1	2	16
235.0	240.0		<0.005	<0.2	10	3	5	24
240.0	245.0		<0.005	<0.2	6	2	1	16
245.0	250.0		<0.005	<0.2	12	5	9	23
250.0	255.0		0.005	<0.2	33	13	40	56
255.0	260.0		<0.005	<0.2	2	2	3	17
260.0	265.0		<0.005	<0.2	5	3	1	16
265.0	270.0		0.014	<0.2	33	4	<1	47
270.0	275.0		0.006	<0.2	15	4	10	31
275.0	280.0		<0.005	<0.2	3	3	3	20
280.0	285.0		<0.005	<0.2	19	5	19	26
285.0	290.0		<0.005	<0.2	9	5	8	19
290.0	295.0		<0.005	<0.2	11	4	5	18
295.0	300.0		<0.005	<0.2	5	1	2	12
300.0	305.0		<0.005	<0.2	5	2	4	13
305.0	310.0		0.01	<0.2	8	2	3	16
310.0	315.0		<0.005	<0.2	8	2	1	24
315.0	320.0		0.017	<0.2	6	2	2	17
320.0	325.0		<0.005	<0.2	9	2	2	20
325.0	330.0		<0.005	<0.2	6	2	1	10
330.0	335.0		<0.005	<0.2	6	1	1	9
335.0	340.0		<0.005	<0.2	8	2	1	18
340.0	345.0		<0.005	<0.2	17	4	5	24
345.0	350.0		0.008	<0.2	51	17	46	66
350.0	355.0		0.009	<0.2	59	21	96	78

Assay Sample Log LRC 06-17

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	45.0	no sample						
45.0	50.0		<0.005	<0.2	20	3	1	26
50.0	55.0		0.006	<0.2	7	2	1	30
55.0	60.0		<0.005	<0.2	20	2	1	25
60.0	65.0		<0.005	<0.2	26	14	3	44
65.0	70.0		<0.005	<0.2	11	90	2	100
70.0	75.0		<0.005	<0.2	17	97	<1	322
75.0	80.0		<0.005	0.5	23	90	1	610
80.0	85.0		<0.005	0.3	23	86	<1	486
85.0	90.0		<0.005	0.2	23	93	<1	323
90.0	95.0		0.007	0.3	22	96	<1	309
95.0	100.0		0.005	<0.2	24	78	<1	258
100.0	105.0		<0.005	0.2	20	88	<1	311
105.0	110.0		0.006	<0.2	15	67	<1	192
110.0	115.0		0.005	0.2	16	69	<1	239
115.0	120.0		<0.005	<0.2	2	105	<1	139
120.0	125.0		<0.005	<0.2	8	95	<1	131
125.0	130.0		<0.005	<0.2	<2	84	<1	88
130.0	135.0		<0.005	<0.2	4	102	<1	89
135.0	140.0		<0.005	<0.2	<2	86	<1	94
140.0	145.0		<0.005	<0.2	8	82	<1	202
145.0	150.0		<0.005	0.3	8	98	<1	158
150.0	155.0		<0.005	<0.2	<2	106	<1	103
155.0	160.0		<0.005	<0.2	8	100	<1	94
160.0	165.0		<0.005	<0.2	2	101	<1	107
165.0	170.0		<0.005	<0.2	4	94	<1	199
170.0	175.0		0.005	0.2	16	89	<1	363
175.0	180.0		0.006	0.3	18	83	<1	435
180.0	185.0		<0.005	0.3	16	83	1	418
185.0	190.0		0.006	<0.2	17	77	<1	313
190.0	195.0		0.006	0.2	13	70	<1	270
195.0	200.0		<0.005	0.2	5	55	<1	125

Assay Sample Log LRC 06-17

page 2

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
200.0	205.0		<0.005	<0.2	4	80	<1	112
205.0	210.0		0.005	<0.2	9	38	<1	141
210.0	215.0		0.006	<0.2	10	48	<1	172
215.0	220.0		0.007	0.2	11	37	<1	120
220.0	225.0		<0.005	<0.2	18	42	<1	154
225.0	230.0		0.005	<0.2	6	40	<1	107
230.0	235.0		<0.005	<0.2	6	37	<1	100
235.0	240.0		<0.005	<0.2	<2	24	<1	76
240.0	245.0		<0.005	<0.2	4	27	<1	83
245.0	250.0		<0.005	<0.2	9	31	<1	99
250.0	255.0		<0.005	<0.2	4	17	<1	55
255.0	260.0		<0.005	<0.2	5	16	<1	59
260.0	265.0		0.005	<0.2	<2	18	<1	68
265.0	270.0		<0.005	<0.2	8	23	<1	79
270.0	275.0		0.005	<0.2	7	39	<1	158
275.0	280.0		<0.005	<0.2	6	22	<1	90
280.0	285.0		<0.005	0.2	8	46	1	173
285.0	290.0		<0.005	<0.2	7	42	<1	133
290.0	295.0		<0.005	<0.2	5	22	<1	81
295.0	300.0		<0.005	0.2	8	40	<1	126
300.0	305.0		<0.005	<0.2	6	35	<1	114
305.0	310.0		<0.005	0.2	12	56	<1	161
310.0	315.0		<0.005	<0.2	13	60	<1	221
315.0	320.0		<0.005	0.2	3	41	<1	137
320.0	325.0		<0.005	<0.2	9	24	<1	118
325.0	330.0		0.006	0.2	20	48	<1	227
330.0	335.0		0.006	0.2	10	38	<1	127
335.0	340.0		0.005	<0.2	12	28	<1	86
340.0	345.0		<0.005	<0.2	<2	22	<1	84
345.0	350.0		<0.005	<0.2	7	16	<1	62
350.0	355.0		<0.005	<0.2	5	12	<1	52
355.0	360.0		<0.005	<0.2	2	32	<1	153
360.0	365.0		<0.005	<0.2	9	30	<1	205

Assay Sample Log LRC 06-18

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	45.0	no sample						
45.0	50.0	no sample						
50.0	55.0		0.009	<0.2	6	62	1	68
55.0	60.0		<0.005	0.2	6	60	<1	71
60.0	65.0		0.005	0.2	8	62	<1	63
65.0	70.0		<0.005	<0.2	7	62	1	69
70.0	75.0		<0.005	<0.2	8	43	1	49
75.0	80.0		0.023	<0.2	6	67	<1	62
80.0	85.0		<0.005	<0.2	3	121	1	51
85.0	90.0		<0.005	<0.2	8	72	<1	85
90.0	95.0		<0.005	<0.2	6	70	<1	84
95.0	100.0		0.005	<0.2	<2	69	<1	85
100.0	105.0		<0.005	0.2	7	68	1	83
105.0	110.0		<0.005	<0.2	8	64	1	67
110.0	115.0		<0.005	0.2	<2	75	<1	92
115.0	120.0		<0.005	0.3	11	60	1	56
120.0	125.0		<0.005	<0.2	13	50	1	48
125.0	130.0		<0.005	<0.2	21	77	<1	98
130.0	135.0		<0.005	0.2	33	76	<1	95
135.0	140.0		<0.005	<0.2	20	74	<1	110
140.0	145.0		0.005	0.2	5	71	1	93
145.0	150.0		<0.005	0.3	6	70	1	75
150.0	155.0		<0.005	<0.2	9	64	<1	66
155.0	160.0		<0.005	<0.2	5	69	<1	73
160.0	165.0		<0.005	0.2	8	66	<1	65
165.0	170.0		<0.005	<0.2	11	79	<1	64
170.0	175.0		<0.005	0.3	9	72	1	68
175.0	180.0		0.006	0.2	6	70	1	70
180.0	185.0		<0.005	<0.2	<2	65	<1	76
185.0	190.0		<0.005	<0.2	3	52	1	68
190.0	195.0		<0.005	<0.2	4	67	<1	71
195.0	200.0		<0.005	<0.2	2	83	1	72

Assay Sample Log LRC 06-18

page 2

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
200.0	205.0		<0.005	<0.2	<2	67	<1	61
205.0	210.0		<0.005	<0.2	2	69	2	79
210.0	215.0		<0.005	<0.2	5	59	<1	80
215.0	220.0		<0.005	<0.2	4	87	1	70
220.0	225.0		<0.005	<0.2	3	65	1	85
225.0	230.0		<0.005	<0.2	2	81	1	89
230.0	235.0		<0.005	<0.2	<2	39	<1	49
235.0	240.0		<0.005	<0.2	<2	13	1	40
240.0	245.0		<0.005	<0.2	<2	7	<1	13
245.0	250.0		<0.005	<0.2	<2	7	<1	17
250.0	255.0		<0.005	<0.2	<2	6	<1	18
255.0	260.0		<0.005	<0.2	4	9	<1	24
260.0	265.0		<0.005	<0.2	3	7	<1	20
265.0	270.0		<0.005	<0.2	13	10	<1	15
270.0	275.0		<0.005	<0.2	<2	6	<1	14
275.0	280.0		<0.005	<0.2	3	10	<1	17
280.0	285.0		<0.005	<0.2	<2	12	<1	27
285.0	290.0		<0.005	<0.2	3	35	1	45
290.0	295.0		<0.005	<0.2	8	113	<1	75
295.0	300.0		<0.005	<0.2	4	96	<1	58
300.0	305.0		<0.005	<0.2	2	162	<1	69
305.0	310.0		<0.005	<0.2	<2	169	<1	71
310.0	315.0		0.005	<0.2	<2	235	<1	77
315.0	320.0		<0.005	<0.2	<2	110	1	61
320.0	325.0		<0.005	<0.2	3	113	<1	67
325.0	330.0		0.007	<0.2	3	147	<1	64
330.0	335.0		<0.005	<0.2	<2	100	<1	63
335.0	340.0		<0.005	<0.2	<2	152	<1	74
340.0	345.0		<0.005	<0.2	3	130	1	63
345.0	350.0		<0.005	<0.2	2	137	<1	65
350.0	355.0		<0.005	<0.2	<2	133	<1	60
355.0	360.0		<0.005	<0.2	5	130	<1	60
360.0	365.0		0.005	<0.2	<2	145	<1	63

Assay Sample Log LRC 06-19

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	35.0	no sample						
35.0	40.0		<0.005	0.2	12	11	3	28
40.0	45.0		<0.005	0.2	8	5	6	41
45.0	50.0		<0.005	<0.2	12	5	6	51
50.0	55.0		<0.005	0.2	83	2	11	56
55.0	60.0		<0.005	0.3	130	3	11	59
60.0	65.0		<0.005	0.2	35	2	3	29
65.0	70.0		<0.005	0.2	51	1	4	31
70.0	75.0		<0.005	0.2	37	1	3	26
75.0	80.0		<0.005	0.2	26	2	6	25
80.0	85.0		<0.005	0.4	27	4	25	69
85.0	90.0		<0.005	0.4	22	3	16	58
90.0	95.0		<0.005	0.2	18	2	4	33
95.0	100.0		<0.005	0.2	10	1	3	18
100.0	105.0		<0.005	<0.2	4	1	3	13
105.0	110.0		<0.005	0.2	5	1	2	15
110.0	115.0		<0.005	0.2	10	3	3	23
115.0	120.0		<0.005	<0.2	16	11	4	49
120.0	125.0		<0.005	0.2	14	3	4	24
125.0	130.0		<0.005	0.2	65	2	13	48
130.0	135.0		<0.005	<0.2	94	3	17	70
135.0	140.0		<0.005	<0.2	26	1	5	18
140.0	145.0		<0.005	0.2	82	1	6	24
145.0	150.0		<0.005	0.2	21	1	6	16
150.0	155.0		<0.005	0.2	24	2	3	12
155.0	160.0		<0.005	0.3	39	2	5	35
160.0	165.0		<0.005	0.2	72	2	7	33
165.0	170.0		<0.005	0.2	71	2	10	22
170.0	175.0		<0.005	<0.2	134	2	17	29
175.0	180.0		<0.005	0.2	96	3	19	41
180.0	185.0		<0.005	<0.2	51	3	6	21
185.0	190.0		<0.005	0.2	21	2	3	14

Assay Sample Log LRC 06-20

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	45.0	no sample						
45.0	50.0		<0.005	<0.2	15	13	52	24
50.0	55.0		<0.005	<0.2	34	14	43	33
50.0	55.0	duplicate	<0.005	<0.2	46	16	39	40
55.0	60.0		<0.005	<0.2	23	13	7	26
60.0	65.0		0.007	<0.2	24	11	30	29
65.0	70.0		<0.005	<0.2	42	7	18	32
70.0	75.0		<0.005	<0.2	27	8	10	29
75.0	80.0		0.006	<0.2	13	10	3	29
80.0	85.0		<0.005	<0.2	18	9	4	29
85.0	90.0		<0.005	<0.2	14	8	2	29
90.0	95.0		<0.005	<0.2	5	9	<1	25
95.0	100.0		<0.005	<0.2	6	8	1	25
100.0	105.0		<0.005	<0.2	6	8	<1	24
100.0	105.0	duplicate	<0.005	<0.2	2	9	<1	26
105.0	110.0		<0.005	<0.2	5	7	<1	26
110.0	115.0		<0.005	<0.2	6	7	<1	26
115.0	120.0		<0.005	<0.2	5	8	<1	26
120.0	125.0		0.006	<0.2	10	72	1	50
125.0	130.0		<0.005	<0.2	5	9	1	23
130.0	135.0		<0.005	<0.2	3	8	3	24
135.0	140.0		<0.005	<0.2	5	8	5	27
140.0	145.0		<0.005	<0.2	5	6	11	24
145.0	150.0		<0.005	<0.2	9	2	1	14
150.0	155.0		<0.005	<0.2	10	2	1	19
150.0	155.0	duplicate	0.007	<0.2	15	2	1	23
155.0	160.0		<0.005	<0.2	2	1	1	14
160.0	165.0		<0.005	<0.2	2	<1	<1	12
165.0	170.0		<0.005	<0.2	3	<1	<1	13
170.0	175.0		<0.005	<0.2	3	<1	<1	13
175.0	180.0		<0.005	<0.2	4	<1	1	11
180.0	185.0		0.012	<0.2	12	1	<1	14

Assay Sample Log LRC 06-21

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	35.0	no sample						
35.0	40.0		0.012	0.2	9	62	<1	69
40.0	45.0		0.01	0.2	5	68	1	85
45.0	50.0		0.008	0.3	7	64	<1	72
50.0	55.0		0.008	0.3	<2	70	<1	71
50.0	55.0	duplicate	0.008	0.3	6	82	<1	79
55.0	60.0		0.005	0.6	4	62	<1	64
60.0	65.0		0.005	0.4	5	50	<1	63
65.0	70.0		0.006	0.3	5	66	<1	73
70.0	75.0		0.007	0.4	2	67	<1	71
75.0	80.0		0.005	0.4	9	57	1	68
80.0	85.0		0.005	0.4	5	59	<1	64
85.0	90.0		0.007	0.2	5	55	<1	62
90.0	95.0		0.005	0.3	<2	64	<1	68
95.0	100.0		<0.005	<0.2	5	51	<1	60
100.0	105.0		0.009	0.2	8	79	<1	94
100.0	105.0	no duplicate						
105.0	110.0		0.007	0.2	3	62	<1	72
110.0	115.0		0.006	0.4	10	64	<1	72
115.0	120.0		<0.005	<0.2	10	47	1	60
120.0	125.0		0.006	0.2	14	55	<1	81
125.0	130.0		<0.005	0.3	3	48	<1	53
130.0	135.0		0.005	0.3	5	60	<1	81
135.0	140.0		<0.005	<0.2	5	57	<1	65
140.0	145.0		0.005	<0.2	7	52	<1	64
145.0	150.0		0.005	<0.2	18	60	<1	88
150.0	155.0		<0.005	<0.2	3	54	<1	61
150.0	155.0	duplicate	<0.005	0.4	4	53	1	62
155.0	160.0		0.007	0.3	14	54	1	78
160.0	165.0		<0.005	0.3	3	67	<1	53
165.0	170.0		<0.005	0.3	8	49	<1	64
170.0	175.0		<0.005	0.4	8	69	<1	61

Assay Sample Log LRC 06-21

page 2

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
175.0	180.0		<0.005	0.2	9	58	<1	67
180.0	185.0		<0.005	0.3	2	54	<1	67
185.0	190.0		<0.005	0.3	6	53	1	62
190.0	195.0		0.008	0.2	2	48	<1	57
195.0	200.0		0.008	0.2	5	52	<1	70
200.0	205.0		0.014	0.2	11	53	<1	73
200.0	205.0	duplicate	0.017	0.4	21	65	<1	90
205.0	210.0		<0.005	0.2	4	46	<1	62
210.0	215.0		<0.005	<0.2	<2	32	<1	34
215.0	220.0		<0.005	<0.2	6	49	<1	34
220.0	225.0		<0.005	0.2	4	49	1	35
225.0	230.0		<0.005	<0.2	4	53	1	36
230.0	235.0		<0.005	<0.2	<2	32	<1	34
235.0	240.0		<0.005	0.2	4	47	1	41
240.0	245.0		<0.005	<0.2	<2	52	1	52
245.0	250.0		<0.005	<0.2	4	32	1	38
250.0	255.0		<0.005	<0.2	7	30	1	39
250.0	255.0	duplicate	0.005	<0.2	12	51	<1	66
255.0	260.0		0.005	0.2	6	49	<1	55
260.0	265.0		0.005	<0.2	6	59	<1	60
265.0	270.0		<0.005	0.2	9	51	<1	61
270.0	275.0		<0.005	0.3	8	48	1	76
275.0	280.0		<0.005	<0.2	5	51	1	72
280.0	285.0		0.005	0.4	9	62	<1	86
285.0	290.0		<0.005	0.2	7	64	<1	82
290.0	295.0		<0.005	0.2	10	56	<1	73
295.0	300.0		<0.005	0.2	3	47	<1	64
300.0	305.0		<0.005	<0.2	2	52	1	67
300.0	305.0	duplicate	0.005	0.2	9	54	1	73
305.0	310.0		<0.005	<0.2	5	49	<1	57
310.0	315.0		<0.005	0.2	11	56	1	67
315.0	320.0		<0.005	<0.2	9	46	<1	59
320.0	325.0		0.006	<0.2	10	48	<1	62

Assay Sample Log LRC 06-21

page 3

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
325.0	330.0		0.005	<0.2	7	45	<1	55
330.0	335.0		<0.005	<0.2	6	42	<1	56
335.0	340.0		<0.005	<0.2	5	34	<1	44
350.0	345.0		0.005	<0.2	10	65	<1	66
345.0	350.0		0.006	<0.2	7	44	1	63
350.0	355.0		0.006	<0.2	8	48	<1	62
350.0	355.0	duplicate	<0.005	<0.2	6	50	<1	63
355.0	360.0		0.008	<0.2	7	37	<1	48
360.0	365.0		0.005	<0.2	8	39	1	52
365.0	370.0		<0.005	<0.2	8	47	<1	64
370.0	375.0		0.006	<0.2	7	53	<1	66
375.0	380.0		<0.005	<0.2	8	52	<1	66
380.0	385.0		<0.005	<0.2	4	46	<1	58
385.0	390.0		0.005	<0.2	8	52	1	68
390.0	395.0		<0.005	0.2	6	45	<1	58
395.0	400.0		<0.005	<0.2	6	46	<1	59
400.0	405.0		<0.005	<0.2	9	78	<1	76
400.0	405.0	duplicate	<0.005	<0.2	6	84	<1	80
405.0	410.0		<0.005	<0.2	7	47	1	61
410.0	415.0		0.006	0.2	5	51	<1	62
415.0	420.0		0.005	<0.2	5	50	<1	59
420.0	425.0		0.005	<0.2	6	45	<1	55
425.0	430.0		0.005	<0.2	6	39	<1	50
430.0	435.0		0.005	<0.2	6	39	1	48
435.0	440.0		<0.005	<0.2	8	49	<1	51
440.0	445.0		0.005	<0.2	7	51	<1	59
445.0	450.0		<0.005	<0.2	6	53	1	58
450.0	455.0		<0.005	0.2	6	52	<1	59
450.0	455.0	duplicate	0.006	<0.2	8	59	1	69
455.0	460.0		0.032	<0.2	6	52	<1	59
460.0	465.0		<0.005	<0.2	8	50	<1	60
465.0	470.0		<0.005	0.2	6	46	<1	50
470.0	475.0		<0.005	<0.2	5	58	<1	65
475.0	480.0		0.01	<0.2	6	58	<1	64

Diamond Drill Log

LRC06-22

Date:

Logged By: DJH

Page 1/ 2

From (ft)	To (ft)	Rock	Struct	@	CA	Alteration							Mineralization							Comments					
						Hfs	SKp	SKr	Mar	Ser	Chl	Si	PY	PO	CP	SL	GL	AS	BN		MG				
0.0	30.0	OB																							Overburden
30.0	175.0	ATc										tr													Chloritic Ash Tuff pale grey/green; loc argillaceous (160-175), foliated/laminated PY as loc disseminations loc white QZ veins
175.0	180.0	A																							Argillite dk grey/black w/ 10% white QZ veining no visible mineralization
180.0	185.0	A										tr													Argillite dk grey/black w/ 70% white QZ veins PY in vnltts?
185.0	195.0	At										tr													Tuffaceous? Argillite black w/ lt green chloritic laminations? PY as disseminated grains
195.0	225.0	A										tr													Argillite black, laminated/foliated PY in vnltts
225.0	330.0	At										tr													Tuffaceous? Argillite a/a 185-195; black w/ lt green chloritic laminations? PY in vnltts
330.0	340.0	A										1													Argillite black PY in vnltts
340.0	370.0	At										tr													Tuffaceous? Argillite a/a 185-195; black w/ lt green chloritic? laminations PY in vnltts

Assay Sample Log LRC 06-22

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	30.0	no sample						
30.0	35.0		<0.005	<0.2	<2	184	1	62
35.0	40.0		<0.005	<0.2	3	203	<1	72
40.0	45.0		<0.005	<0.2	6	284	<1	60
45.0	50.0		<0.005	<0.2	4	177	<1	54
45.0	50.0	duplicate	<0.005	<0.2	6	214	<1	59
50.0	55.0		0.011	<0.2	2	190	<1	56
55.0	60.0		<0.005	<0.2	4	113	<1	65
60.0	65.0		<0.005	<0.2	3	230	<1	66
65.0	70.0		<0.005	<0.2	2	225	<1	62
70.0	75.0		<0.005	<0.2	<2	144	<1	55
75.0	80.0		<0.005	<0.2	<2	149	<1	62
80.0	85.0		<0.005	<0.2	<2	158	<1	68
85.0	90.0		<0.005	<0.2	4	184	<1	66
90.0	95.0		<0.005	<0.2	3	161	<1	73
95.0	100.0		<0.005	<0.2	3	153	<1	71
100.0	105.0		<0.005	<0.2	<2	143	<1	64
105.0	110.0		<0.005	<0.2	<2	131	<1	56
110.0	115.0		<0.005	<0.2	4	163	<1	56
115.0	120.0		0.006	<0.2	2	450	<1	57
120.0	125.0		<0.005	<0.2	4	206	<1	68
125.0	130.0		<0.005	<0.2	<2	41	<1	28
130.0	135.0		<0.005	<0.2	4	163	<1	55
135.0	140.0		<0.005	<0.2	3	372	<1	59
140.0	145.0		<0.005	<0.2	5	143	<1	61
145.0	150.0		<0.005	<0.2	2	143	<1	54
145.0	150.0	duplicate	0.006	<0.2	3	149	<1	54
150.0	155.0		<0.005	<0.2	<2	113	<1	63
155.0	160.0		<0.005	<0.2	2	124	<1	56
160.0	165.0		<0.005	<0.2	4	136	<1	68
165.0	170.0		<0.005	<0.2	6	173	<1	70
170.0	175.0		<0.005	<0.2	8	178	<1	66

Assay Sample Log LRC 06-22

page 2

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
175.0	180.0		<0.005	<0.2	5	84	<1	81
180.0	185.0		<0.005	0.2	4	71	<1	58
185.0	190.0		0.011	<0.2	9	118	<1	74
190.0	195.0		0.012	<0.2	17	172	<1	77
195.0	200.0		0.005	0.3	7	125	<1	92
195.0	200.0	duplicate	0.006	<0.2	6	126	<1	96
200.0	205.0		<0.005	0.3	<2	82	<1	139
205.0	210.0		<0.005	0.3	9	84	<1	103
210.0	215.0		<0.005	<0.2	<2	104	<1	115
215.0	220.0		<0.005	<0.2	2	77	<1	105
220.0	225.0		<0.005	<0.2	2	78	<1	122
225.0	230.0		0.006	<0.2	3	164	<1	77
230.0	235.0		<0.005	<0.2	<2	172	<1	72
235.0	240.0		<0.005	<0.2	<2	163	<1	71
240.0	245.0		<0.005	<0.2	<2	98	<1	59
245.0	250.0		<0.005	<0.2	<2	127	<1	62
245.0	250.0	duplicate	<0.005	<0.2	6	130	<1	62
250.0	255.0		<0.005	<0.2	3	133	<1	54
250.0	260.0		<0.005	<0.2	8	154	<1	63
260.0	265.0		<0.005	<0.2	<2	100	<1	67
265.0	270.0		0.006	<0.2	<2	83	<1	73
270.0	275.0		<0.005	<0.2	4	111	<1	71
275.0	280.0		<0.005	<0.2	<2	130	<1	65
280.0	285.0		0.01	<0.2	<2	111	<1	66
285.0	290.0		<0.005	<0.2	<2	115	<1	61
290.0	295.0		<0.005	<0.2	<2	116	<1	64
295.0	300.0		<0.005	<0.2	2	86	<1	57
300.0	305.0		<0.005	<0.2	<2	102	<1	72
305.0	310.0		<0.005	<0.2	<2	115	<1	69
300.0	315.0		<0.005	<0.2	<2	106	<1	64
315.0	320.0		<0.005	<0.2	7	119	<1	64
320.0	325.0		<0.005	<0.2	<2	127	<1	71
325.0	330.0		<0.005	<0.2	<2	116	<1	64

Assay Sample Log LRC 06-22

page 3

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
330.0	335.0		0.009	0.2	<2	113	<1	76
335.0	340.0		0.014	<0.2	<2	102	<1	74
340.0	345.0		0.02	<0.2	<2	162	<1	82
345.0	350.0		0.01	<0.2	4	172	1	74
350.0	355.0		<0.005	<0.2	3	185	<1	62
355.0	360.0		0.008	<0.2	<2	178	<1	67
360.0	365.0		<0.005	<0.2	<2	165	<1	68
350.0	370.0		<0.005	<0.2	<2	213	<1	76
370.0	375.0		<0.005	<0.2	4	405	<1	97
375.0	380.0		<0.005	<0.2	<2	401	<1	74
380.0	385.0		<0.005	<0.2	<2	398	<1	65
385.0	390.0		<0.005	<0.2	2	339	<1	73
390.0	395.0		<0.005	<0.2	4	181	<1	66
395.0	400.0		<0.005	<0.2	<2	179	<1	61
400.0	405.0		<0.005	<0.2	2	109	<1	61
405.0	410.0		<0.005	<0.2	4	155	<1	58
410.0	415.0		0.005	<0.2	2	167	<1	59
415.0	420.0		0.013	<0.2	<2	174	<1	69
400.0	425.0		<0.005	<0.2	2	179	<1	72
425.0	430.0		<0.005	<0.2	9	147	<1	63
430.0	435.0		<0.005	<0.2	10	115	<1	64
435.0	440.0		<0.005	<0.2	10	106	1	59
440.0	445.0		<0.005	<0.2	14	147	<1	69
445.0	450.0		<0.005	<0.2	9	173	<1	78
450.0	455.0		<0.005	<0.2	6	190	<1	83
455.0	460.0		0.011	<0.2	<2	202	<1	91
460.0	465.0		<0.005	<0.2	8	184	2	84
465.0	470.0		<0.005	<0.2	5	171	<1	78
450.0	475.0		<0.005	<0.2	6	130	<1	67
450.0	480.0		<0.005	<0.2	12	150	2	81
480.0	485.0		<0.005	<0.2	7	173	2	62
485.0	490.0		<0.005	<0.2	8	202	<1	59
490.0	495.0		<0.005	<0.2	9	105	<1	60
495.0	500.0		<0.005	<0.2	13	214	1	65

Assay Sample Log LRC 06-23

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	30.0	no sample						
30.0	35.0		<0.005	<0.2	7	5	6	19
35.0	40.0		<0.005	<0.2	8	4	6	34
40.0	45.0		<0.005	<0.2	8	9	4	38
45.0	50.0		<0.005	<0.2	4	4	4	20
45.0	50.0	duplicate	0.006	<0.2	<2	4	5	24
50.0	55.0		0.005	<0.2	<2	2	7	25
55.0	60.0		0.007	0.2	10	3	5	25
60.0	65.0		0.008	<0.2	25	3	5	50
65.0	70.0		<0.005	<0.2	10	1	3	25
70.0	75.0		<0.005	<0.2	6	1	4	25
75.0	80.0		0.007	<0.2	7	1	1	16
80.0	85.0		<0.005	<0.2	7	1	1	17
85.0	90.0		<0.005	<0.2	<2	1	1	9
90.0	95.0		<0.005	<0.2	3	1	1	13
95.0	100.0		<0.005	<0.2	<2	<1	2	8
95.0	100.0	duplicate	<0.005	<0.2	<2	2	2	10
100.0	105.0		<0.005	<0.2	3	1	2	13
105.0	110.0		<0.005	<0.2	4	1	3	10
110.0	115.0		<0.005	<0.2	4	1	3	11
115.0	120.0		<0.005	<0.2	4	2	2	14
120.0	125.0		<0.005	<0.2	3	1	1	15
125.0	130.0		<0.005	<0.2	11	1	2	13
130.0	135.0		<0.005	<0.2	5	1	2	12
135.0	140.0		<0.005	<0.2	9	2	3	15
140.0	145.0		<0.005	<0.2	<2	1	4	17
145.0	150.0		<0.005	<0.2	8	1	6	22
145.0	150.0	duplicate	<0.005	<0.2	4	2	6	23
150.0	155.0		<0.005	0.2	10	2	6	27
155.0	160.0		<0.005	<0.2	3	1	4	13
160.0	165.0		<0.005	<0.2	5	2	3	16
165.0	170.0		<0.005	<0.2	3	1	1	12

Assay Sample Log LRC06-23

Page: 1

Sample No.	From (m)	To (m)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
	0.0	9.1	no sample						
	9.1	10.7		0.002	0.1	7	5	6	19
	10.7	12.2		0.002	0.1	8	4	6	34
	12.2	13.7		0.002	0.1	8	9	4	38
	13.7	15.2		0.002	0.1	4	4	4	20
	13.7	15.2	dup	0.006	0.1	1	4	5	24
	15.2	16.8		0.005	0.1	1	2	7	25
	16.8	18.3		0.007	0.2	10	3	5	25
	18.3	19.8		0.008	0.1	25	3	5	50
	19.8	21.3		0.002	0.1	10	1	3	25
	21.3	22.9		0.002	0.1	6	1	4	25
	22.9	24.4		0.007	0.1	7	1	1	16
	24.4	25.9		0.002	0.1	7	1	1	17
	25.9	27.4		0.002	0.1	1	1	1	9
	27.4	29.0		0.002	0.1	3	1	1	13
	29.0	30.5		0.002	0.1	1	0.5	2	8
	29.0	30.5	dup	0.002	0.1	1	2	2	10
	30.5	32.0		0.002	0.1	3	1	2	13
	32.0	33.5		0.002	0.1	4	1	3	10
	33.5	35.1		0.002	0.1	4	1	3	11
	35.1	36.6		0.002	0.1	4	2	2	14
	36.6	38.1		0.002	0.1	3	1	1	15
	38.1	39.6		0.002	0.1	11	1	2	13
	39.6	41.1		0.002	0.1	5	1	2	12
	41.1	42.7		0.002	0.1	9	2	3	15
	42.7	44.2		0.002	0.1	1	1	4	17
	44.2	45.7		0.002	0.1	8	1	6	22
	44.2	45.7	dup	0.002	0.1	4	2	6	23
	45.7	47.2		0.002	0.2	10	2	6	27
	47.2	48.7		0.002	0.1	3	1	4	13
	48.7	50.2		0.002	0.1	5	2	3	16
	50.2	51.7		0.002	0.1	3	1	1	12

Assay Sample Log LRC 06-24

page 1

From (ft)	To (ft)	Sample Type	ppm Au	ppm Ag	ppm As	ppm Cu	ppm Hg	ppm Zn
0.0	30.0	no sample						
30.0	35.0		0.036	<0.2	58	3	7	27
35.0	40.0		0.008	<0.2	45	<1	10	27
40.0	45.0		0.03	<0.2	247	11	11	37
45.0	50.0		0.051	0.2	1330	127	92	144
45.0	50.0	duplicate	0.006	<0.2	1235	121	79	135
50.0	55.0		<0.005	<0.2	372	24	145	58
55.0	60.0		<0.005	<0.2	406	22	299	60
60.0	65.0		0.061	0.3	299	18	917	58
65.0	70.0		<0.005	<0.2	270	17	678	58
70.0	75.0		0.006	<0.2	174	7	6330	58
75.0	80.0		<0.005	<0.2	97	4	1930	44
80.0	85.0		<0.005	<0.2	92	4	222	43
85.0	90.0		0.156	0.2	71	4	1400	28
90.0	95.0		<0.005	<0.2	24	<1	344	39
95.0	100.0		<0.005	<0.2	19	<1	177	20
95.0	100.0	duplicate	<0.005	<0.2	15	<1	198	20
100.0	105.0		<0.005	<0.2	15	<1	113	17
105.0	110.0		<0.005	<0.2	16	<1	34	15
110.0	115.0		<0.005	<0.2	9	<1	33	12
115.0	120.0		<0.005	<0.2	3	<1	25	13
120.0	125.0		<0.005	<0.2	10	<1	25	14
125.0	130.0		0.039	<0.2	5	<1	16	16
130.0	135.0		<0.005	<0.2	5	<1	13	13
135.0	140.0		<0.005	<0.2	2	<1	9	13
140.0	145.0		<0.005	<0.2	10	<1	10	14
145.0	150.0		0.016	<0.2	2	<1	15	17
145.0	150.0	duplicate	0.018	<0.2	5	<1	10	16
150.0	155.0		0.131	<0.2	3	<1	17	16
155.0	160.0		<0.005	<0.2	5	2	7	18
160.0	165.0		<0.005	<0.2	3	2	7	15
165.0	170.0		0.015	<0.2	<2	2	5	9

Appendix III

2006 Bedrock Trenching Assay Logs

Appendix IV

ALS Chemex Analytical Technique



Sample Preparation Package – PREP-31
Standard Sample Preparation: Dry, Crush, Split and Pulverize

Sample is dried and the entire sample is crushed to better than 70% passing a 2 mm (Tyler 10 mesh) screen. A split of up to 250 grams is taken and pulverized to better than 85% passing a 75 micron (Tyler 200 mesh) screen.

ALS Chemex Method Code	Description
LOG-22	Sample is logged in tracking system and a bar code label is attached.
CRU-31	Fine crushing of rock chip and drill samples to better than 70% of the sample passing 2 mm.
SPL-21	Split sample using riffle splitter.
PUL-31	A sample split of up to 250 g is pulverized to better than 85% of the sample passing 75 microns.



Sample Preparation Package – PREP-41
Dry sample and dry-sieve to –180 micron

Sample is dried and then dry-sieved using a 180 micron (Tyler 80 mesh) screen. The plus fraction is retained unless disposal is requested. This method is appropriate for soil or sediment samples up to one kilogram in weight.

ALS Chemex Method Code	Description
LOG-22	Sample is logged in tracking system and a bar code label is attached.
SCR-41	Sample is dry-sieved to –180 micron and both the plus and minus fractions are retained.



**Fire Assay Procedure – Ag-GRA21, Ag-GRA22, Au-GRA21 & Au-GRA22
Precious Metals Gravimetric Analysis Methods**

Sample Decomposition: Fire Assay Fusion

Analytical Method: Gravimetric

A prepared sample is fused with a mixture of lead oxide, sodium carbonate, borax, silica and other reagents in order to produce a lead button. The lead button containing the precious metals is cupelled to remove the lead. The remaining gold and silver bead is parted in dilute nitric acid, annealed and weighed as gold. Silver, if requested, is then determined by the difference in weights.

Method Code	Element	Sample Weight	Lower Reporting Limit	Upper Reporting Limit	Units
Ag-GRA21	Silver	30 grams	5	10,000	ppm
Ag-GRA22	Silver	50 grams	5	10,000	ppm
Au-GRA21	Gold	30 grams	0.05	1000	ppm
Au-GRA22	Gold	50 grams	0.05	1000	ppm



Fire Assay Procedure – Au-AA23 and Au-AA24
Fire Assay Fusion, AAS Finish

Sample Decomposition: Fire Assay Fusion

Analytical Method: Atomic Absorption Spectroscopy (AAS)

A prepared sample is fused with a mixture of lead oxide, sodium carbonate, borax, silica and other reagents as required, inquarted with 6 mg of gold-free silver and then cupelled to yield a precious metal bead.

The bead is digested in 0.5 ml dilute nitric acid in the microwave oven, 0.5 ml concentrated hydrochloric acid is then added and the bead is further digested in the microwave at a lower power setting. The digested solution is cooled, diluted to a total volume of 4 ml with de-mineralized water, and analyzed by atomic absorption spectroscopy against matrix-matched standards.

ALS Chemex Method Code	Element	Symbol	Sample Weight	Lower Reporting Limit	Upper Reporting Limit	Units
Au-AA23	Gold	Au	30 g	0.005	10.0	ppm
Au-AA24	Gold	Au	50 g	0.005	10.0	ppm



Assay Procedure – ME-AA46
**Evaluation of Ores and High Grade Materials by Aqua Regia
 Digestion – AAS**

Sample Decomposition: Aqua Regia Digestion

Analytical Method: Atomic Absorption Spectroscopy (AAS)

A prepared sample (0.4 to 2.00 grams) is digested with concentrated nitric acid for one half hour. After cooling, hydrochloric acid is added to produce aqua regia and the mixture is then digested for an additional hour and a half. An ionization suppressant is added if molybdenum is to be measured. The resulting solution is diluted to volume (100 or 250 ml) with demineralized water, mixed and then analyzed by atomic absorption spectrometry against matrix-matched standards.

ALS Chemex Method Code	Element	Symbol	Detection Limit	Upper Limit	Units
As-AA46	Arsenic	As	0.01	30	%
Bi-AA46	Bismuth	Bi	0.001	30	%
Cd-AA46	Cadmium	Cd	0.001	10	%
Co-AA46	Cobalt	Co	0.01	50	%
Cu-AA46	Copper	Cu	0.01	50	%
Fe-AA46	Iron	Fe	0.01	30	%
Pb-AA46	Lead	Pb	0.01	30	%
Mo-AA46	Molybdenum	Mo	0.001	10	%
Mn-AA46	Manganese	Mn	0.01	50	%
Ni-AA46	Nickel	Ni	0.01	50	%
Ag-AA46	Silver	Ag	1	1500	ppm
Zn-AA46	Zinc	Zn	0.01	30	%



Geochemical Procedure - ME-ICP41
Trace Level Methods Using Conventional ICP-AES Analysis

Sample Decomposition: Nitric Aqua Regia Digestion

Analytical Method: Inductively Coupled Plasma - Atomic Emission Spectroscopy (ICP - AES)

A prepared sample (0.50 grams) is digested with aqua regia for at least one hour in a graphite heating block. After cooling, the resulting solution is diluted to 12.5 ml with demineralized water, mixed and analyzed by inductively coupled plasma-atomic emission spectrometry. The analytical results are corrected for inter-element spectral interferences.

Element	Symbol	Detection Limit	Upper Limit	Units
Aluminum*	Al	0.01	15	%
Antimony	Sb	2	10,000	ppm
Arsenic	As	2	10,000	ppm
Barium*	Ba	10	10,000	ppm
Beryllium*	Be	0.5	100	ppm
Bismuth	Bi	2	10,000	ppm
Boron*	B	10	10,000 ppm	ppm
Cadmium	Cd	0.5	500	ppm
Calcium*	Ca	0.01	15	%
Chromium*	Cr	1	10,000	ppm
Cobalt	Co	1	10,000	ppm
Copper	Cu	1	10,000	ppm
Gallium*	Ga	10	10,000	ppm
Iron	Fe	0.01	15	%
Lanthanum*	La	10	10,000	ppm
Lead	Pb	2	10,000	ppm
Magnesium*	Mg	0.01	15	%
Manganese	Mn	5	10,000	ppm
Mercury	Hg	1	10,000	ppm
Molybdenum	Mo	1	10,000	ppm



Geochemical Procedure - ME-ICP41
Trace Level Methods Using Conventional ICP-AES Analysis (con't)

Element	Symbol	Detection Limit	Upper Limit	Units
Nickel	Ni	1	10,000	ppm
Phosphorus	P	10	10,000	ppm
Potassium*	K	0.01	10	%
Scandium*	Sc	1	10,000	ppm
Silver	Ag	0.2	100	ppm
Sodium*	Na	0.01	10 %	%
Strontium*	Sr	1	10,000	ppm
Sulfur	S	0.01	10	%
Thallium*	Tl	10	10,000	ppm
Titanium*	Ti	0.01	10	%
Tungsten*	W	10	10,000	ppm
Uranium	U	10	10,000	ppm
Vanadium	V	1	10,000	ppm
Zinc	Zn	2	10,000	ppm

*Elements for which the digestion is possibly incomplete.

Appendix V

**CDN Resource Laboratories Ltd. - Standard CDN-CGS-7, CDN-CGS-10,
and Blank CDN-BL2**

CDN Resource Laboratories Ltd.

10945-B River Road, Delta, B.C., V4C 2R8, 604 596-2245, Fax: 604 588-3960

ORE REFERENCE STANDARD: CDN-CGS-7

Recommended values and the “Between Lab” Two Standard Deviations

Copper concentration: $1.01 \pm 0.07 \%$

Gold concentration $0.95 \pm 0.08 \text{ g/t}$

PREPARED BY: CDN Resource Laboratories Ltd.

CERTIFIED BY: Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia

INDEPENDENT GEOCHEMIST: Dr. Barry Smee., Ph.D., P. Geo.

METHOD OF PREPARATION:

Reject ore material was dried, crushed, pulverized and then passed through a 200 mesh screen. The +200 material was discarded. The -200 material was mixed for 5 days in a rotary mixer. After internal assaying to test for homogeneity, splits were taken and sent to 11 laboratories for round robin assaying.

ORIGIN OF REFERENCE MATERIAL:

The ore was supplied by bcMetals Corporation from the Red Chris Property in British Columbia. Most of the mineralization is closely associated with individual and sheeted quartz (\pm carbonate) veining and quartz (\pm carbonate) stockwork zones. It occurs as disseminations and fracture coatings. Pyrite, chalcopyrite and lesser bornite are the principal sulphide minerals. Gold occurs as electrum spatially and genetically associated with the copper mineralization.

Approximate chemical composition is as follows:

	Percent			Percent
SiO ₂	58.2		MgO	1.9
Al ₂ O ₃	9.6		K ₂ O	3.6
Fe ₂ O ₃	13.0		TiO ₂	0.3
CaO	3.1		LOI	7.0
Na ₂ O	1.5			

Statistical Procedures:

The mean and standard deviation for all data was calculated. Outliers were defined as samples beyond the mean ± 2 Standard Deviations from all data. These outliers were removed from the data and a new mean and standard deviation was determined. This method is different from that used by Government agencies in that the actual “between-laboratory” standard deviation is used in the calculations. This produces upper and lower limits that reflect actual individual analyses rather than a grouped set of analyses. The limits can therefore be used to monitor accuracy from individual analyses, unlike the Certified Limits published on other standards.

Results from round-robin assaying are presented on the following page:

Assay Procedures: **Au:** Fire assay pre-concentration, AA or ICP finish (30g sub-sample).

Cu: 4-acid digestion, AA or ICP finish.

STANDARD REFERENCE MATERIAL CDN-CGS-7

	Lab. 1	Lab. 2	Lab. 3	Lab. 4	Lab. 5	Lab. 6	Lab. 7	Lab. 8	Lab. 9	Lab. 10	Lab. 11
	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t
	0.94	0.94	0.91	0.9	0.96	0.96	0.94	1.06	0.99	1.01	0.96
	1.00	1.01	1.00	0.94	0.96	0.98	0.92	1.02	0.96	0.92	0.87
	0.96	0.96	0.92	0.94	0.95	0.92	0.96	1.04	0.92	0.98	0.89
	0.95	1.01	0.95	0.94	1.05	0.94	0.94	0.99	0.93	0.95	0.90
	0.98	1.02	0.96	0.94	0.96	0.97	0.89	1.02	0.95	0.99	0.94
	0.95	1.02	0.92	I.S.	0.93	0.94	0.96	1.04	0.91	1.06	0.95
	0.94	0.96	0.86	0.89	0.97	0.93	0.90	1.07	0.94	1.06	1.00
	0.92	1.04	0.87	0.92	0.99	0.96	0.87	1.00	0.92	0.93	0.92
	0.99	1.01	0.91	0.95	0.93	0.92	0.92	1.02	0.97	0.98	0.99
	0.94	1.02	0.97	0.92	0.96	0.96	0.89	0.96	0.94	1.07	0.95
Mean	0.96	1.00	0.92	0.93	0.97	0.95	0.92	1.02	0.94	1.00	0.94
Std. Dev.	0.025	0.033	0.044	0.022	0.034	0.022	0.031	0.033	0.025	0.054	0.042
%RSD	2.65	3.35	4.72	2.36	3.56	2.30	3.38	3.20	2.65	5.47	4.50
	Lab. 1	Lab. 2	Lab. 3	Lab. 4	Lab. 5	Lab. 6	Lab. 7	Lab. 8	Lab. 9	Lab. 10	Lab. 11
	Cu (%)	Cu (%)	Cu (%)	Cu (%)	Cu (%)	Cu (%)	Cu (%)	Cu (%)	Cu (%)	Cu (%)	Cu (%)
	1.02	1.01	1.01	1.02	1.03	1.03	0.94	1.04	1.02	1.00	0.95
	1.02	1.01	1.01	0.96	1.03	1.04	0.95	1.04	1.04	1.00	0.96
	1.01	0.98	1.01	1.01	1.03	1.06	0.94	1.05	1.03	0.99	0.95
	1.03	0.99	1.01	1.06	1.03	1.06	0.95	1.05	1.03	0.97	0.94
	1.01	1.00	1.01	1.01	1.04	1.05	0.95	1.04	1.02	0.99	0.99
	1.02	1.02	1.00	0.99	1.04	1.05	0.94	1.04	1.03	1.01	0.95
	1.02	1.00	1.01	0.96	1.03	1.05	0.95	1.06	1.01	0.98	0.92
	1.03	1.00	1.00	0.97	1.03	1.03	0.95	1.05	1.00	1.01	0.98
	1.02	1.01	0.99	0.99	1.04	1.06	0.95	1.04	1.01	1.00	0.94
	1.02	1.00	0.99	0.99	1.04	1.04	0.95	1.05	1.02	1.00	0.94
Mean	1.02	1.00	1.00	1.00	1.03	1.05	0.95	1.05	1.02	1.00	0.95
Std. Dev.	0.0062	0.0090	0.0084	0.0306	0.0052	0.0116	0.0048	0.0070	0.0120	0.0115	0.0204
%RSD	0.61	0.90	0.84	3.07	0.50	1.11	0.51	0.67	1.18	1.16	2.15

STANDARD REFERENCE MATERIAL CDN-CGS-7

Participating Laboratories:

(not in same order as listed in table of results)

Acme Analytical Laboratories Ltd.
Actlabs - Skyline, Arizona
Assayers Canada Ltd., Vancouver
ALS Chemex Laboratories, North Vancouver
Alex Stewart, Argentina
Genalysis Laboratory Services Pty. Ltd., Australia
GTK Laboratory, (Geological Survey of Finland)
OMAC Laboratories Ltd., Ireland
SGS-XRAL, Toronto
SGS-Lakefield, Ontario
TSL Laboratories, Saskatoon

Legal Notice:

This certificate and the reference material described in it have been prepared with due care and attention. However CDN Resource Laboratories Ltd. or Barry Smee accept no liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by

Duncan Sanderson, B.Sc.
Licensed Assayer of British Columbia



Geochemist

Dr. Barry Smee, Ph.D., P. Geo.

CDN Resource Laboratories Ltd.

10945-B River Road, Delta, B.C., V4C 2R8, 604-540-2233, Fax: 604-588-3960

ORE REFERENCE STANDARD: CDN-CGS-10

Recommended values and the “Between Lab” Two Standard Deviations

Copper concentration: 1.55 ± 0.07 %

Gold concentration 1.73 ± 0.15 g/t

PREPARED BY: CDN Resource Laboratories Ltd.

CERTIFIED BY: Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia

INDEPENDENT GEOCHEMIST: Dr. Barry Smee., Ph.D., P. Geo.

DATE OF CERTIFICATION: February 8, 2006

METHOD OF PREPARATION:

Reject ore material was dried, crushed, pulverized and then passed through a 200 mesh screen. The +200 material was discarded. The -200 material was mixed for 5 days in a rotary mixer. After internal assaying to test for homogeneity, splits were taken and sent to 12 laboratories for round robin assaying.

ORIGIN OF REFERENCE MATERIAL:

The ore was supplied by bcMetals Corporation from the Red Chris Property in British Columbia. Most of the mineralization is closely associated with individual and sheeted quartz (\pm carbonate) veining and quartz (\pm carbonate) stockwork zones. It occurs as disseminations and fracture coatings. Pyrite, chalcopyrite and lesser bornite are the principal sulphide minerals. Gold occurs as electrum spatially and genetically associated with the copper mineralization.

Approximate chemical composition is as follows:

	Percent		Percent
SiO ₂	60.5	MgO	1.9
Al ₂ O ₃	12.7	K ₂ O	3.1
Fe ₂ O ₃	9.1	TiO ₂	0.4
CaO	3.6	LOI	5.3
Na ₂ O	1.8		

Statistical Procedures:

The mean and standard deviation for all data was calculated. Outliers were defined as samples beyond the mean ± 2 Standard Deviations from all data. These outliers were removed from the data and a new mean and standard deviation was determined. This method is different from that used by Government agencies in that the actual “between-laboratory” standard deviation is used in the calculations. This produces upper and lower limits that reflect actual individual analyses rather than a grouped set of analyses. The limits can therefore be used to monitor accuracy from individual analyses, unlike the Certified Limits published on other standards.

Results from round-robin assaying are presented on the following page:

Assay Procedures: **Au:** Fire assay pre-concentration, AA or ICP finish (30g sub-sample).
Cu: 4-acid digestion, AA or ICP finish.

STANDARD REFERENCE MATERIAL CDN-CGS-10

	Lab. 1	Lab. 2	Lab. 3	Lab. 4	Lab. 5	Lab. 6	Lab. 7	Lab. 8	Lab. 9	Lab 10	Lab 11	Lab 12
	Au (g/t)	Au (g/t)	Au (g/t)	Au (g/t)	Au (g/t)	Au (g/t)	Au (g/t)	Au (g/t)	Au (g/t)	Au (g/t)	Au (g/t)	Au (g/t)
	1.58	1.75	1.68	1.65	1.77	1.69	1.82	1.65	2.01	1.78	1.62	1.75
	1.67	1.88	1.67	1.77	1.71	1.64	1.75	1.68	1.98	1.96	1.62	1.70
	1.63	1.76	1.76	1.78	1.82	1.78	1.70	1.76	1.83	1.78	1.80	1.70
	1.65	1.64	1.73	1.70	1.73	1.63	1.70	1.66	1.90	1.75	1.68	1.71
	1.66	1.64	1.66	1.81	1.76	1.65	1.69	1.81	2.09	1.85	1.70	1.61
	1.72	1.73	1.64	1.70	1.66	1.62	1.68	1.82	1.84	1.82	1.70	1.68
	1.68	1.71	1.64	1.78	1.86	1.74	1.76	1.83	1.85	1.92	1.72	1.71
	1.71	1.76	1.64	1.81	1.74	1.82	1.78	1.64	2.02	1.72	1.70	1.68
	1.57	1.65	1.67	1.77	1.70	1.61	1.73	1.72	1.89	1.72	1.70	1.75
	1.65	1.81	1.70	1.77	1.68	1.66	1.70	1.72	1.92	1.85	1.76	1.69
Mean	1.65	1.73	1.68	1.75	1.75	1.68	1.72	1.74	1.93	1.81	1.70	1.70
Std. Dev.	0.049	0.076	0.040	0.056	0.061	0.072	0.036	0.071	0.088	0.081	0.055	0.040
%RSD	2.96	4.41	2.41	3.17	3.51	4.29	2.09	4.10	4.55	4.49	3.23	2.34
	Cu (%)	Cu (%)	Cu (%)	Cu (%)	Cu (%)	Cu (%)	Cu (%)	Cu (%)	Cu (%)	Cu (%)	Cu (%)	Cu (%)
	1.56	1.565	1.51	1.51	1.55	1.55	1.51	1.58	1.56	1.541	1.637	1.540
	1.55	1.555	1.52	1.52	1.56	1.55	1.51	1.63	1.55	1.565	1.607	1.520
	1.57	1.515	1.52	1.50	1.53	1.56	1.51	1.59	1.63	1.541	1.605	1.540
	1.54	1.555	1.51	1.50	1.53	1.55	1.51	1.59	1.58	1.585	1.611	1.540
	1.58	1.565	1.52	1.50	1.54	1.56	1.50	1.60	1.63	1.541	1.587	1.529
	1.57	1.530	1.51	1.51	1.53	1.55	1.50	1.58	1.60	1.581	1.611	1.518
	1.55	1.570	1.52	1.52	1.57	1.55	1.51	1.63	1.63	1.600	1.615	1.537
	1.56	1.565	1.54	1.51	1.57	1.55	1.51	1.60	1.64	1.568	1.61	1.532
	1.54	1.565	1.51	1.54	1.54	1.55	1.51	1.60	1.63	1.574	1.605	1.544
	1.52	1.520	1.52	1.52	1.53	1.56	1.50	1.61	1.67	1.571	1.575	1.539
Mean	1.554	1.551	1.518	1.513	1.545	1.555	1.507	1.601	1.612	1.567	1.606	1.534
Std. Dev.	0.018	0.021	0.009	0.013	0.017	0.005	0.005	0.018	0.036	0.020	0.016	0.009
%RSD	1.14	1.34	0.61	0.83	1.07	0.31	0.36	1.12	2.22	1.30	1.02	0.58

STANDARD REFERENCE MATERIAL CDN-CGS-10

Participating Laboratories:

(not in same order as listed in table of results)

Acme Analytical Laboratories Ltd., Vancouver
Assayers Canada Ltd., Vancouver
ALS Chemex Laboratories, North Vancouver
Alex Stewart Assayers, Argentina
EcoTech Laboratory, Kamloops, B.C.
Genalysis Laboratory Services Pty. Ltd., Australia
GTK Laboratory, (Geological Survey of Finland)
International Plasma Labs. Ltd., Vancouver
OMAC Laboratories Ltd., Ireland
SGS-XRAL, Toronto
Teck Cominco - Global Discovery Laboratory, Vancouver
TSL Laboratories, Saskatoon

Legal Notice:

This certificate and the reference material described in it have been prepared with due care and attention. However CDN Resource Laboratories Ltd. or Barry Smee accept no liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by

Duncan Sanderson, B.Sc.
Licensed Assayer of British Columbia



Geochemist

Dr. Barry Smee, Ph.D., P. Geo.

CDN Resource Laboratories Ltd.

10945-B River Road, Delta, B.C., Canada, V4C 2R8, 604-540-2233, Fax: 604-588-3960 (www.cdnlabs.com)

ORE REFERENCE STANDARD: CDN-FCM-2

Recommended values and the "Between Lab" Two Standard Deviations

Gold 1.37 ± 0.12 g/t
Silver 73.9 ± 7.3 g/t
Copper 0.756 ± 0.046 %
Lead 0.479 ± 0.038 %
Zinc 1.739 ± 0.104 %

PREPARED BY: CDN Resource Laboratories Ltd.
CERTIFIED BY: Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia
INDEPENDENT GEOCHEMIST: Dr. Barry Smee., Ph.D., P. Geo.
DATE OF CERTIFICATION: February 20, 2006

METHOD OF PREPARATION:

Reject ore material was dried, crushed, pulverized and then passed through a 200 mesh screen. The +200 material was discarded. The -200 material was mixed for 5 days in a rotary mixer. Splits were taken and sent to eleven laboratories for round robin assaying. The material has been packaged in nominal 100g lots in tin-top kraft bags which have been individually vacuum-sealed in polyethylene bags.

ORIGIN OF REFERENCE MATERIAL:

The ore was supplied by Hunter Dickinson (Farallon) from their Campo Morado property in Mexico. The Campo Morado precious-metal-bearing, volcanogenic massive sulphide deposits occur in a lower Cretaceous bimodal, calc-alkaline volcanic sequence. Most deposits occur in the upper part of a sequence of felsic flows and heterolithic volcanoclastic rocks or at its contact with overlying chert and argillite. Gold, silver, zinc, and lead are associated with pyrite, quartz, ankerite, sphalerite, chalcopyrite and galena, with minor tennantite-freibergite, arsenopyrite, and pyrrotite.

Approximate chemical composition is as follows:

Standard FCM-2 is a high sulphide material with approximately 35% sulphur.

Statistical Procedures:

The mean and standard deviation for all data was calculated. Outliers were defined as samples beyond the mean ± 2 Standard Deviations from all data. These outliers were removed from the data and a new mean and standard deviation was determined. The Au data from one laboratory and the Ag data from another laboratory were excluded as they did not pass the "t" test. This method is different from that used by Government agencies in that the actual "between-laboratory" standard deviation is used in the calculations. This produces upper and lower limits that reflect actual individual analyses rather than a grouped set of analyses. The limits can therefore be used to monitor accuracy from individual analyses, unlike the Confidence Limits published on other standards.

Results from round-robin assaying are presented on subsequent pages:

Assay Procedures:

Au: Fire assay pre-concentration, AA or ICP finish (10g sub-sample).
Ag, Cu, Pb, Zn: 4-acid digestion, AA or ICP finish.

STANDARD REFERENCE MATERIAL CDN-FCM-2

	Lab 1	Lab 2	Lab 3	Lab 4	Lab 5	Lab 6	Lab 7	Lab 8	Lab 9	Lab 10	Lab 11
	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t
FCM-2-1	1.34	1.29	1.30	1.38	1.44	1.53	1.49	1.33	1.27	1.35	1.40
FCM-2-2	1.35	1.36	1.33	1.33	1.40	1.46	1.50	1.35	1.33	1.35	1.38
FCM-2-3	1.35	1.36	1.29	1.33	1.70	1.37	1.47	1.39	1.30	1.35	1.38
FCM-2-4	1.33	1.28	1.22	1.35	1.43	1.39	1.43	1.35	1.37	1.35	1.36
FCM-2-5	1.45	1.28	1.32	1.35	1.36	1.37	1.54	1.55	1.35	1.35	1.38
FCM-2-6	1.40	1.42	1.25	1.41	1.35	1.36	1.44	1.41	1.32	1.38	1.38
FCM-2-7	1.43	1.33	1.32	1.40	1.29	1.41	1.47	1.36	1.31	1.38	1.37
FCM-2-8	1.35	1.34	1.26	1.49	1.56	1.36	1.45	1.30	1.45	1.38	1.39
FCM-2-9	1.37	1.28	1.31	1.42	1.51	1.34	1.46	1.37	1.37	1.32	1.38
FCM-2-10	1.33	1.28	1.32	1.39	1.35	1.04	1.47	1.33	1.45	1.38	1.38
Mean	1.37	1.32	1.29	1.38	1.44	1.36	1.47	1.37	1.35	1.36	1.38
Std. Devn.	0.0424	0.0483	0.0368	0.0484	0.1219	0.1270	0.0319	0.0693	0.0603	0.0202	0.0105
% RSD	3.10	3.65	2.85	3.50	8.47	9.32	2.17	5.04	4.46	1.49	0.76
	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t
FCM-2-1	70.8	69.8	80	76	77.9	69	77.7	74.8	70.9	75.6	71.4
FCM-2-2	71.0	72.5	79	75	78.3	70	78.2	74.3	70.0	75.2	72.1
FCM-2-3	68.9	67.8	79	76	77.8	72	78.2	74.5	70.6	75.6	71.9
FCM-2-4	69.9	69.2	80	75	77.0	69	77.7	73.5	70.4	75.0	72.7
FCM-2-5	70.6	69.5	81	76	78.2	72	77.5	74.4	70.7	76.9	73.1
FCM-2-6	70.7	70.0	80	74	80.9	69	76.7	73.8	70.2	75.4	73.8
FCM-2-7	70.2	67.6	80	75	77.8	72	79.7	75.1	70.1	74.9	71.6
FCM-2-8	71.0	68.2	80	74	77.3	70	77.0	74.3	70.8	75.0	70.0
FCM-2-9	69.8	68.0	80	76	78.0	70	78.7	73.4	70.2	75.9	70.1
FCM-2-10	70.3	73.4	81	76	76.1	69	75.5	73.3	70.7	75.6	70.0
Mean	70.3	69.6	80.0	75.3	77.9	70.2	77.7	74.1	70.5	75.5	71.7
Std. Devn.	0.6546	1.9715	0.6667	0.8233	1.2329	1.3166	1.1484	0.6132	0.3204	0.6090	1.3334
% RSD	0.93	2.83	0.83	1.09	1.58	1.88	1.48	0.83	0.45	0.81	1.86

STANDARD REFERENCE MATERIAL CDN-FCM-2

	Lab 1	Lab 2	Lab 3	Lab 4	Lab 5	Lab 6	Lab 7	Lab 8	Lab 9	Lab 10	Lab 11
	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu
FCM-2-1	0.680	0.74	0.791	0.750	0.745	0.742	0.753	0.76	0.71	0.783	0.78
FCM-2-2	0.669	0.76	0.782	0.747	0.744	0.756	0.768	0.76	0.71	0.770	0.77
FCM-2-3	0.676	0.76	0.775	0.751	0.741	0.767	0.764	0.76	0.70	0.795	0.77
FCM-2-4	0.681	0.77	0.782	0.741	0.737	0.747	0.727	0.76	0.71	0.763	0.78
FCM-2-5	0.678	0.75	0.791	0.744	0.750	0.756	0.768	0.76	0.71	0.769	0.78
FCM-2-6	0.677	0.77	0.786	0.728	0.750	0.759	0.766	0.75	0.71	0.772	0.77
FCM-2-7	0.675	0.77	0.801	0.742	0.737	0.751	0.744	0.75	0.71	0.763	0.77
FCM-2-8	0.677	0.77	0.801	0.747	0.743	0.758	0.732	0.76	0.71	0.764	0.79
FCM-2-9	0.676	0.78	0.790	0.754	0.738	0.744	0.731	0.75	0.71	0.781	0.78
FCM-2-10	0.679	0.77	0.802	0.767	0.743	0.747	0.736	0.76	0.71	0.777	0.78
Mean	0.677	0.764	0.790	0.747	0.743	0.753	0.749	0.757	0.709	0.774	0.777
Std. Devn.	0.0033	0.0117	0.0092	0.0100	0.0048	0.0078	0.0168	0.0048	0.0032	0.0104	0.0067
% RSD	0.49	1.54	1.16	1.34	0.64	1.04	2.25	0.64	0.45	1.34	0.87
	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb
FCM-2-1	0.47	0.43	0.52	0.48	0.488	0.45	0.472	0.48	0.50	0.454	0.49
FCM-2-2	0.47	0.43	0.51	0.48	0.487	0.45	0.496	0.49	0.50	0.449	0.48
FCM-2-3	0.47	0.43	0.51	0.48	0.484	0.47	0.474	0.49	0.49	0.46	0.50
FCM-2-4	0.48	0.44	0.53	0.48	0.484	0.45	0.458	0.49	0.50	0.452	0.50
FCM-2-5	0.48	0.43	0.52	0.48	0.491	0.46	0.478	0.49	0.50	0.455	0.49
FCM-2-6	0.47	0.44	0.52	0.46	0.492	0.45	0.476	0.49	0.49	0.453	0.50
FCM-2-7	0.47	0.43	0.52	0.48	0.481	0.46	0.464	0.48	0.49	0.453	0.48
FCM-2-8	0.48	0.43	0.53	0.47	0.484	0.46	0.484	0.48	0.49	0.451	0.49
FCM-2-9	0.46	0.43	0.52	0.48	0.483	0.46	0.494	0.48	0.49	0.459	0.49
FCM-2-10	0.47	0.43	0.54	0.48	0.486	0.45	0.48	0.48	0.50	0.456	0.49
Mean	0.47	0.43	0.52	0.48	0.49	0.46	0.48	0.49	0.50	0.45	0.49
Std. Devn.	0.0063	0.0042	0.0092	0.0067	0.0035	0.0070	0.0119	0.0053	0.0053	0.0034	0.0074
% RSD	1.34	0.98	1.76	1.41	0.73	1.53	2.49	1.09	1.06	0.75	1.50
	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn
FCM-2-1	1.67	1.770	1.82	1.82	1.70	1.78	1.815	1.73	1.75	1.65	1.75
FCM-2-2	1.65	1.820	1.80	1.80	1.71	1.81	1.746	1.73	1.70	1.67	1.70
FCM-2-3	1.68	1.788	1.80	1.80	1.70	1.81	1.764	1.71	1.67	1.67	1.72
FCM-2-4	1.66	1.839	1.83	1.76	1.69	1.78	1.731	1.73	1.69	1.66	1.76
FCM-2-5	1.66	1.773	1.81	1.78	1.72	1.79	1.786	1.71	1.71	1.67	1.73
FCM-2-6	1.69	1.825	1.78	1.74	1.72	1.81	1.750	1.72	1.72	1.65	1.72
FCM-2-7	1.67	1.803	1.77	1.77	1.69	1.81	1.723	1.72	1.72	1.69	1.73
FCM-2-8	1.65	1.801	1.78	1.80	1.70	1.85	1.680	1.71	1.73	1.66	1.71
FCM-2-9	1.68	1.818	1.76	1.80	1.71	1.78	1.744	1.71	1.71	1.71	1.75
FCM-2-10	1.66	1.826	1.81	1.82	1.71	1.76	1.745	1.71	1.70	1.7	1.73
Mean	1.67	1.81	1.80	1.79	1.71	1.80	1.75	1.72	1.71	1.67	1.73
Std. Devn.	0.0134	0.0234	0.0227	0.0260	0.0108	0.0253	0.0361	0.0092	0.0221	0.0206	0.0189
% RSD	0.80	1.30	1.26	1.45	0.63	1.41	2.07	0.53	1.29	1.23	1.09

STANDARD REFERENCE MATERIAL CDN-FCM-2

Participating Laboratories:

(not in same order as listed in table of results)

Acme Analytical Laboratories Ltd., Vancouver
Assayers Canada Ltd., Vancouver
ALS Chemex Laboratories, North Vancouver
Eco-Tech Laboratories Ltd., Kamloops
Genalysis Laboratory Services Ltd., Perth
GTK Laboratory, Finland
International Plasma Laboratories Ltd., Vancouver
OMAC Laboratory Ltd., Ireland
SGS-XRAL, Toronto
Teck Cominco - Global Discovery Laboratory, Vancouver
TSL Laboratories Ltd., Saskatoon

Legal Notice:

This certificate and the reference material described in it have been prepared with due care and attention. However CDN Resource Laboratories Ltd. or Barry Smee accept no liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by

Duncan Sanderson, B.Sc.
Licensed Assayer of British Columbia



Geochemist

Dr. Barry Smee, Ph.D., P. Geo.

CDN Resource Laboratories Ltd.

10945-B River Road, Delta, B.C., V4C 2R8, Ph: 604-540-2233, Fax: 604-588-3960

STANDARD REFERENCE MATERIAL: CDN-BL2

Recommended values:

Gold concentration: < 0.01 g/t

Platinum concentration: < 0.01 g/t

Palladium concentration: < 0.01 g/t

PREPARED BY: CDN Resource Laboratories Ltd.
CERTIFIED BY: Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia
INDEPENDENT GEOCHEMIST: Dr. Barry Smee., Ph. D., P. Geo.
DATE OF CERTIFICATION: March 15, 2006

ORIGIN OF REFERENCE MATERIAL:

Standard CDN-BL2 was prepared using a blank granitic material.

METHOD OF PREPARATION:

The granitic material was dried, crushed, pulverized and then passed through a 200 mesh screen. The +200 material was discarded. The -200 (<75 micron) material was mixed for 5 days in a rotary mixer. Splits were taken and sent to 6 commercial laboratories for round robin assaying. Round robin results are displayed below:

APPROXIMATE CHEMICAL COMPOSITION:

	Percent			Percent
SiO ₂	69.6		Na ₂ O	4.5
Al ₂ O ₃	14.0		MgO	0.9
Fe ₂ O ₃	4.7		K ₂ O	1.9
CaO	2.4		TiO ₂	0.4
MnO	0.1		LOI	0.9

Statistical Procedures:

There was no statistical analysis performed on the data. All analytical results were less than the recommended values.

Participating Laboratories: (not in same order as table of assays)

Acme Analytical Laboratories Ltd.
Assayers Canada Ltd., Vancouver
ALS Chemex Laboratories, North Vancouver
International Plasma Laboratories Ltd., Vancouver
Teck Cominco - Global Discovery Laboratory, Vancouver
TSL Laboratories, Saskatoon

Assay Procedure: assays were fire assay, AA or ICP finish on 30g samples.

STANDARD REFERENCE MATERIAL: CDN-BL2

	Lab. 1	Lab. 2	Lab. 3	Lab. 4	Lab. 5	Lab. 6
Sample	Au ppb	Au ppb	Au ppb	Au ppb	Au ppb	Au ppb
CDN-BL2-1	< 10	< 10	<2	2	< 5	5
CDN-BL2-2	< 10	< 10	<2	1	< 5	6
CDN-BL2-3	< 10	< 10	<2	1	< 5	4
CDN-BL2-4	< 10	< 10	<2	1	< 5	5
CDN-BL2-5	< 10	< 10	<2	1	< 5	5
CDN-BL2-6	< 10	< 10	<2	1	< 5	3
CDN-BL2-7	< 10	< 10	<2	2	< 5	4
CDN-BL2-8	< 10	< 10	<2	1	< 5	4
CDN-BL2-9	< 10	< 10	<2	1	< 5	7
CDN-BL2-10	< 10	< 10	<2	1	< 5	4
	Pt ppb	Pt ppb	Pt ppb	Pt ppb	Pt ppb	Pt ppb
CDN-BL2-1	< 10	< 10	4	< 5	< 10	< 5
CDN-BL2-2	< 10	< 10	3	< 5	< 10	< 5
CDN-BL2-3	< 10	< 10	< 2	< 5	< 10	< 5
CDN-BL2-4	< 10	< 10	< 2	< 5	< 10	< 5
CDN-BL2-5	< 10	10	3	< 5	< 10	< 5
CDN-BL2-6	< 10	< 10	< 2	< 5	< 10	< 5
CDN-BL2-7	< 10	< 10	3	< 5	< 10	< 5
CDN-BL2-8	< 10	< 10	< 2	< 5	< 10	< 5
CDN-BL2-9	< 10	< 10	< 2	< 5	< 10	< 5
CDN-BL2-10	< 10	< 10	2	7	< 10	< 5
	Pd ppb	Pd ppb	Pd ppb	Pd ppb	Pd ppb	Pd ppb
CDN-BL2-1	< 10	< 10	2	1	< 5	< 2
CDN-BL2-2	< 10	< 10	5	< 1	< 5	< 2
CDN-BL2-3	< 10	< 10	<2	1	< 5	< 2
CDN-BL2-4	< 10	10	<2	< 1	< 5	< 2
CDN-BL2-5	< 10	< 10	2	< 1	< 5	< 2
CDN-BL2-6	< 10	< 10	8	< 1	< 5	< 2
CDN-BL2-7	< 10	< 10	3	1	< 5	< 2
CDN-BL2-8	< 10	< 10	5	< 1	< 5	< 2
CDN-BL2-9	< 10	< 10	2	1	< 5	< 2
CDN-BL2-10	< 10	< 10	2	< 1	< 5	< 2

Legal Notice:

This certificate and the reference material described in it have been prepared with due care and attention. However CDN Resource Laboratories Ltd. nor Barry Smee accept any liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by

Duncan Sanderson, Licensed Assayer of British Columbia

Geochemist



Barry Smee, Ph.D., P. Geo.

Appendix VI

2006 Diamond Drilling - ALS Chemex Certificates of Analysis

VA06080883 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 196
 DATE RECEIVED : 2006-08-21 DATE FINALIZED : 2006-09-23
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE	Au	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn	Ag-AA46	Zn-AA46	Cu-AA46	Pb-AA46	
DESCRIPT	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
369568	1.9	2.1	0.15	>10000	<10	30	<0.5	13	17.7	77.1	9	4	77	5.16	<10	<1	0.06	10	4.71	4070	3	0.03	20	660	150	5.4	69	2	248	<0.01	<10	10	11	<10	8680					
369569	0.62	27.3	0.03	6300	<10	10	<0.5	128	7.1	731	<1	<1	198	23.5	<10	<1	0.01	<10	1.98	11750	1	0.01	<1	300	2240	>10.0	379	<1	107	<0.01	10	<10	5	<10	>10000		9.32			
369570	0.033	0.4	0.12	1215	<10	50	<0.5	<2	>25.0	11.5	<1	9	18	1.95	<10	<1	0.05	<10	4.92	2770	1	0.03	3	830	48	0.9	21	2	245	<0.01	<10	10	10	<10	1590					
369571	0.336	5.1	0.05	>10000	<10	20	<0.5	37	22.5	229	<1	2	249	8.92	<10	<1	0.02	<10	1.33	5930	14	0.03	2	810	246	>10.0	169	1	173	<0.01	<10	30	7	<10	>10000		2.72			
369572	0.11	13.9	0.16	1360	<10	10	<0.5	76	23	11	1	8	278	6.69	<10	<1	0.09	10	2.82	3120	7	0.03	18	770	200	4.2	218	2	170	<0.01	10	20	32	120	1865					
369573	0.084	6.2	0.13	>10000	<10	20	<0.5	39	9.99	274	9	6	1380	31.3	10	<1	0.04	10	0.52	6590	7	0.03	8	1830	356	>10.0	979	3	80	<0.01	10	10	20	80	>10000		1.58			
369574	0.171	3.7	0.03	990	<10	10	<0.5	20	>25.0	21.9	1	5	123	4.88	<10	<1	0.01	10	2.28	5150	2	0.03	7	380	124	2.6	208	2	411	<0.01	10	10	8	<10	3150					
369575	1.215	71.7	0.1	1750	<10	<10	<0.5	57	1.45	77.4	94	20	7730	31.3	<10	11	0.01	<10	0.62	1295	13	<0.01	15	130	4520	>10.0	250	<1	27	<0.01	20	<10	8	<10	>10000		1.87			
369576	0.066	1.9	0.33	810	<10	20	<0.5	10	2.03	13.4	3	8	114	8.63	<10	<1	0.1	<10	3.7	3310	11	0.02	15	540	94	3.3	51	7	42	<0.01	<10	10	28	<10	2070					
369577	0.806	10	0.45	>10000	<10	20	<0.5	108	15.3	13.5	7	15	243	5.86	<10	<1	0.21	10	4.27	1650	9	0.03	12	1930	312	3.66	428	3	175	<0.01	10	30	48	280	2040					
369578	0.449	4.7	0.04	>10000	<10	10	<0.5	11	6.89	8	9	<1	536	30	<10	<1	0.03	<10	0.81	2640	4	0.02	16	150	95	>10.0	252	1	77	<0.01	20	10	7	<10	1590					
369579	0.104	5.3	0.28	1165	<10	20	<0.5	21	8.24	163.5	2	2	374	11.9	<10	<1	0.14	<10	5.33	6470	8	0.02	13	470	252	8.06	71	6	141	<0.01	10	<10	25	<10	>10000					
369580	1.465	89.4	0.01	>10000	<10	<10	<0.5	18	5.93	>1000	<1	<1	1280	31.3	<10	2	<0.01	<10	0.15	1520	<1	0.02	<1	50	2890	>10.0	>10000	<1	22	<0.01	<10	10	5	40	>10000		9.86			
369581	0.51	>100	0.01	>10000	<10	20	<0.5	2	16.4	65.9	<1	4	390	20.4	<10	<1	0.01	10	0.49	5890	<1	0.03	1	170	>10000	>10.0	>10000	<1	109	<0.01	<10	10	<1	<10	5830	192		2.62		
369582	0.053	14.5	0.07	3850	<10	60	<0.5	<2	>25.0	168	<1	10	35	3.32	<10	<1	0.01	10	5.19	5780	<1	0.03	2	320	2110	3.5	2330	<1	151	<0.01	<10	10	8	<10	>10000		1.39			
369583	0.274	5.3	0.08	7960	<10	10	<0.5	3	1.01	7.9	23	<1	2300	44.9	<10	<1	0.03	<10	0.18	160	1	0.01	8	4330	226	>10.0	201	<1	14	<0.01	10	<10	3	<10	1130					
369584	0.397	2.6	0.56	>10000	<10	40	<0.5	35	2.11	2.7	17	1	237	14.6	<10	<1	0.15	10	0.89	442	13	0.01	20	5290	221	>10.0	182	3	67	<0.01	<10	<10	24	<10	321					
369585	0.11	2.2	0.77	2180	<10	60	<0.5	22	3.3	17.1	11	12	325	11.2	<10	<1	0.17	10	0.86	457	5	0.03	24	920	320	6.72	205	4	66	0.01	<10	<10	33	<10	2530					
369586	0.063	3.4	0.2	2760	10	80	<0.5	35	0.86	1.2	4	7	83	5.2	<10	<1	0.07	10	0.3	220	5	0.01	14	420	1445	3.22	1150	1	48	<0.01	<10	<10	7	<10	127					
369587	0.025	1	0.56	772	10	90	<0.5	9	0.48	<0.5	2	9	79	5.55	<10	<1	0.07	10	0.51	255	11	0.01	24	170	172	3.01	134	1	27	<0.01	<10	<10	8	<10	63					
369588	3.87	23.2	0.07	>10000	<10	20	<0.5	41	4.47	821	2	<1	589	22.3	<10	<1	0.02	<10	1.72	1055	<1	0.01	4	1270	1585	>10.0	145	<1	230	<0.01	<10	<10	2	<10	>10000		10.5			
369589	1.095	31.7	0.15	9630	10	20	<0.5	483	0.94	4	33	<1	1320	33.8	<10	<1	0.02	<10	0.19	188	1	0.01	13	100	2580	>10.0	2270	<1	34	<0.01	10	<10	<1	<10	371					

VA06087901 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 20
 DATE RECEIVED : 2006-08-22 DATE FINALIZED : 2006-09-26
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE	Au	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn	Cu-AA46
DESCRIP	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	%
B369590	0.712	6.2	0.77	28	<10	30	<0.5	3	6.94	<0.5	16	19	4500	8.47	<10	<1	0.03	10	0.6	1200	26	0.05	31	500	6	6.53	3	6	217	0.09	<10	<10	66	30	46	
B369591	0.932	8.8	0.99	33	<10	20	<0.5	10	7.01	<0.5	21	24	6980	17.1	10	<1	0.15	10	0.92	1150	18	0.05	46	890	6	>10.0	3	5	171	0.09	<10	<10	78	40	55	
B369592	0.424	4	0.47	32	<10	20	<0.5	3	6.58	<0.5	20	4	3060	11.15	<10	<1	0.02	<10	0.85	895	47	0.03	14	880	6	>10.0	<2	2	160	0.03	<10	<10	26	20	38	
B369593	0.3	3.4	1.15	21	<10	30	<0.5	5	4.94	<0.5	12	7	2230	8.59	<10	<1	0.04	20	0.99	947	30	0.09	14	1460	8	7.17	<2	2	191	0.1	<10	<10	37	20	50	
B369594	0.093	1.7	1.23	39	<10	100	0.6	<2	3.83	<0.5	11	23	1025	6.2	<10	<1	0.25	10	0.7	650	11	0.05	28	470	5	3.89	8	7	78	0.07	<10	<10	50	10	83	
B369595	0.029	0.5	1.9	59	<10	170	0.8	<2	1.67	<0.5	8	36	372	2.63	10	<1	0.57	10	0.98	295	12	0.11	29	430	5	1.2	3	9	80	0.12	<10	<10	70	<10	41	
B369596	0.136	1.8	1.26	59	<10	20	<0.5	4	8.1	<0.5	6	27	969	8.56	10	<1	0.06	10	0.54	1530	93	0.02	12	560	8	4.71	2	6	42	0.17	<10	<10	60	10	44	
B369597	0.027	0.4	1.45	111	<10	40	<0.5	<2	11.25	0.5	3	23	232	9.19	10	<1	0.03	10	0.75	1560	79	0.02	7	640	6	2.02	<2	5	29	0.13	<10	<10	62	60	34	
B369598	0.041	1	2.29	80	<10	50	<0.5	2	11.05	<0.5	2	22	408	8.45	10	<1	0.03	10	0.62	1005	32	0.04	15	1600	11	1.45	2	2	80	0.07	<10	<10	84	70	37	
B369599	0.01	<0.2	0.66	1010	<10	<10	<0.5	3	18.9	0.7	2	12	126	18.4	10	<1	0.01	10	0.36	1745	13	0.02	2	490	8	1.5	<2	1	15	0.01	<10	10	32	290	19	
B369600	<0.005	<0.2	0.93	3	<10	60	<0.5	<2	0.65	<0.5	4	17	33	3.02	<10	<1	0.07	10	0.47	549	5	0.08	11	440	5	0.04	<2	3	27	0.1	<10	<10	25	<10	37	
B369601	1.71	5.6	0.46	21	<10	120	<0.5	11	1.68	0.7	10	38	>10000	9.63	<10	2	0.29	<10	0.8	804	15	0.03	15	450	16	3.47	26	4	49	<0.01	<10	<10	49	10	85	
B369602	0.048	<0.2	0.7	792	<10	10	<0.5	4	15.2	<0.5	1	18	62	13.5	10	<1	0.02	10	0.47	1535	125	0.02	2	880	4	1.76	2	<1	20	0.02	<10	10	43	290	20	
B369603	0.018	<0.2	0.59	793	<10	10	<0.5	5	11.9	<0.5	1	12	231	10.8	10	<1	0.09	10	0.43	1225	34	0.03	3	1170	6	1.47	2	1	28	0.05	<10	10	37	210	22	
B369604	0.019	<0.2	0.62	707	<10	20	<0.5	4	12.85	<0.5	1	15	129	11.55	10	<1	0.05	10	0.43	1300	37	0.03	<1	2620	6	1.89	2	1	30	0.04	<10	10	32	240	26	
B369605	0.029	0.7	0.73	871	<10	10	<0.5	5	16	<0.5	1	20	408	17.2	10	<1	0.02	10	0.28	1640	7	0.02	1	2810	6	2.5	3	<1	23	0.01	<10	20	42	330	24	
B369606	<0.005	<0.2	0.85	876	<10	10	<0.5	3	17	<0.5	1	25	22	15.8	20	<1	0.01	10	0.25	1675	5	0.01	<1	4630	4	<0.01	2	<1	22	0.01	<10	20	43	280	20	
B369607	0.006	<0.2	0.65	1005	<10	<10	<0.5	3	17.2	<0.5	1	20	78	16.7	20	<1	0.01	10	0.21	1765	9	0.02	<1	1840	6	0.6	2	<1	17	0.01	<10	10	31	330	17	
B369608	<0.005	<0.2	0.47	1230	<10	<10	<0.5	<2	17.4	<0.5	1	12	180	17.1	10	1	0.01	10	0.13	1700	7	0.02	1	690	5	0.5	3	<1	12	<0.01	<10	20	17	350	16	
B369609	0.007	<0.2	0.74	1245	<10	<10	<0.5	2	17.2	<0.5	<1	13	30	17	10	<1	0.01	20	0.11	1875	10	0.02	<1	860	6	0.8	5	<1	16	0.01	<10	10	25	320	12	

Appendix VII

2006 Reverse Circulation Drilling - ALS Chemex Certificates of Analysis

VA06081734 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 24
 DATE RECEIVED : 2006-08-14 DATE FINALIZED : 2006-09-15
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE	Au-AA23	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41
DESCRIPTION	Au	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn	
	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
LRC06-06 80-85	<0.005	<0.2	0.18	26	<10	30	<0.5	<2	>25.0	0.9	1	4	4	0.29	<10	1	0.02	<10	0.16	106	<1	0.02	3	130	3	<0.01	2	1	150	0.02	<10	<10	8	<10	25	
LRC06-06 90-95	0.014	<0.2	0.07	4	<10	20	<0.5	<2	>25.0	<0.5	<1	2	2	0.11	<10	1	0.01	<10	0.1	39	<1	0.02	1	80	2	<0.01	<2	<1	144	0.01	<10	<10	3	<10	7	
LRC06-06 95-100	0.006	<0.2	0.02	4	<10	20	<0.5	<2	>25.0	<0.5	<1	1	<1	0.04	<10	1	<0.01	<10	0.07	29	<1	0.01	1	50	<2	<0.01	<2	<1	156	<0.01	<10	<10	1	<10	5	
LRC06-06 100-105	0.006	<0.2	0.01	6	<10	10	<0.5	<2	>25.0	0.5	<1	1	<1	0.02	<10	<1	<0.01	<10	0.07	29	<1	0.01	<1	50	<2	<0.01	<2	<1	145	<0.01	<10	<10	1	<10	5	
LRC06-06 105-110	<0.005	0.3	0.02	3	<10	10	<0.5	<2	>25.0	0.5	<1	1	<1	0.02	<10	<1	<0.01	<10	0.05	25	<1	0.01	<1	50	2	<0.01	<2	<1	161	<0.01	<10	<10	1	<10	4	
LRC06-06 110-115	<0.005	<0.2	0.03	4	<10	10	<0.5	<2	>25.0	0.5	<1	1	<1	0.03	<10	1	0.01	<10	0.08	15	<1	0.01	1	40	2	<0.01	<2	<1	204	<0.01	<10	<10	2	<10	6	
LRC06-06 115-120	<0.005	<0.2	0.01	2	<10	10	<0.5	<2	>25.0	0.5	<1	1	<1	0.02	<10	<1	<0.01	<10	0.07	16	<1	0.02	1	30	<2	<0.01	<2	<1	169	<0.01	<10	<10	1	<10	4	
LRC06-06 120-125	<0.005	0.3	0.01	5	<10	10	<0.5	<2	>25.0	<0.5	<1	1	<1	0.02	<10	<1	<0.01	<10	0.07	16	<1	0.01	1	30	<2	<0.01	<2	<1	219	<0.01	<10	<10	2	<10	4	
LRC06-06 125-130	<0.005	<0.2	0.02	3	<10	20	<0.5	<2	>25.0	<0.5	<1	3	<1	0.05	<10	1	<0.01	<10	0.09	20	<1	0.01	2	30	<2	<0.01	2	<1	218	<0.01	<10	<10	5	<10	9	
LRC06-06 130-135	<0.005	<0.2	0.04	6	<10	40	<0.5	<2	>25.0	0.6	<1	4	<1	0.08	<10	1	<0.01	<10	0.11	48	<1	0.01	5	60	<2	<0.01	3	<1	203	<0.01	<10	<10	3	<10	14	
LRC06-06 135-140	0.005	<0.2	0.06	6	<10	30	<0.5	<2	>25.0	0.8	<1	6	1	0.16	<10	1	0.01	<10	0.14	79	<1	0.01	6	60	<2	<0.01	4	1	164	<0.01	<10	<10	5	<10	19	
LRC06-06 140-145	0.005	<0.2	0.05	9	<10	40	<0.5	<2	>25.0	0.6	<1	7	<1	0.13	<10	1	0.01	<10	0.14	60	<1	0.02	6	50	<2	<0.01	4	<1	181	<0.01	<10	<10	5	<10	21	
LRC06-06 145-150	0.006	<0.2	0.07	34	<10	30	<0.5	<2	>25.0	0.6	8	28	2	0.28	<10	2	0.01	<10	0.13	134	<1	0.02	88	80	2	<0.01	21	2	184	<0.01	<10	<10	6	<10	36	
LRC06-06 150-155	<0.005	<0.2	0.05	10	<10	40	<0.5	<2	>25.0	0.6	1	8	1	0.18	<10	1	0.01	<10	0.15	60	<1	0.02	11	50	2	<0.01	6	1	186	<0.01	<10	<10	5	<10	17	
LRC06-06 155-160	0.006	<0.2	0.13	4	<10	40	<0.5	<2	>25.0	0.5	1	8	2	0.26	<10	1	0.01	<10	0.18	77	<1	0.01	6	70	2	<0.01	<2	1	171	0.02	<10	<10	8	<10	13	
LRC06-06 160-165	<0.005	0.2	0.09	24	<10	80	<0.5	<2	>25.0	0.6	4	36	5	0.54	<10	1	0.01	<10	1.5	196	<1	0.02	96	110	12	<0.01	9	2	178	0.01	<10	<10	9	<10	41	
LRC06-06 165-170	0.011	<0.2	0.52	19	<10	210	<0.5	<2	21	<0.5	10	89	11	1.3	<10	2	0.05	<10	2.84	336	<1	0.02	172	230	5	<0.01	4	4	165	0.03	<10	<10	24	<10	34	
LRC06-06 170-175	0.007	0.8	1.13	21	<10	190	<0.5	<2	17	0.9	31	245	40	2.28	<10	3	0.12	<10	3.24	507	1	0.02	445	260	35	<0.01	9	10	158	0.01	<10	<10	44	<10	88	
LRC06-06 175-180	0.008	<0.2	0.64	4	10	60	<0.5	<2	12.05	<0.5	35	314	10	2.63	<10	1	0.03	<10	7.1	544	<1	0.02	749	150	3	0.07	<2	5	130	0.04	<10	<10	24	<10	25	
LRC06-06 180-185	<0.005	<0.2	0.19	3	<10	40	<0.5	<2	10.4	<0.5	52	214	9	2.92	<10	9	0.01	<10	7.17	566	<1	0.01	1140	30	<2	0.25	<2	6	166	0.01	<10	<10	15	<10	13	
LRC06-06 185-190	0.01	<0.2	0.37	4	<10	160	<0.5	<2	16.2	<0.5	32	163	7	2.31	<10	5	0.02	<10	5.74	531	<1	0.02	666	130	<2	<0.01	<2	5	138	0.02	<10	<10	19	<10	18	
LRC06-06 190-195	<0.005	<0.2	0.3	10	20	60	<0.5	<2	7.56	<0.5	48	315	10	3.22	<10	2	0.01	<10	11.25	677	<1	0.01	1060	20	<2	0.3	2	5	123	<0.01	<10	<10	14	<10	12	
LRC06-06 195-200	0.01	<0.2	0.41	3	10	70	<0.5	<2	12.2	<0.5	51	379	13	3	<10	2	0.01	<10	7.43	618	<1	0.02	1090	40	<2	0.13	<2	6	157	0.01	<10	<10	20	<10	14	
LRC06-06 200-205	0.005	<0.2	2.77	5	20	40	<0.5	<2	6.45	<0.5	42	379	52	3.86	<10	1	0.01	<10	11.1	611	<1	0.02	702	30	<2	0.08	<2	17	113	0.02	<10	<10	121	<10	19	

VA06081735 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 95
 DATE RECEIVED : 2006-08-14 DATE FINALIZED : 2006-09-28
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE DESCRIPTION	Au-AA23	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41
	Au ppm	Ag ppm	Al %	As ppm	B ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Ti %	Ti ppm	U ppm	V ppm	W ppm	Zn ppm										
LRC06-05 20-25	0.005	<0.2	0.36	41	<10	40	<0.5	<2	>25.0	0.7	1	11	7	0.23	<10	5	0.1	10	0.08	47	<1	0.02	10	240	5	<0.01	6	1	134	<0.01	<10	<10	6	<10	31										
LRC06-05 435-440	<0.005	<0.2	0.01	3	<10	<10	<0.5	<2	>25.0	<0.5	1	1	1	0.02	<10	<1	<0.01	<10	0.05	16	<1	0.01	3	60	2	<0.01	7	<1	84	<0.01	<10	10	2	<10	8										

VA06081735 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 95
 DATE RECEIVED : 2006-08-14 DATE FINALIZED : 2006-09-28
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE DESCRIPTION	Au- ppm	AA23 ppm	ME-ICP41 ppm	ME-ICP41 %	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm	ME-ICP41 ppm
LRC06-05 440-445	<0.005	<0.2	0.02	3	<10	<10	<0.5	<2	>25.0	<0.5	1	1	1	0.02	<10	<1	<0.01	<10	0.06	13	<1	0.01	3	60	2	<0.01	4	<1	77	<0.01	<10	10	2	<10	8
LRC06-05 445-450	<0.005	<0.2	0.03	<2	<10	<10	<0.5	<2	>25.0	<0.5	1	1	2	0.08	<10	<1	0.01	<10	0.06	13	<1	0.01	3	60	<2	<0.01	4	<1	90	<0.01	<10	10	2	<10	13
LRC06-05 450-455	<0.005	<0.2	0.04	4	<10	<10	<0.5	<2	>25.0	<0.5	2	1	2	0.15	<10	<1	0.01	<10	0.06	14	<1	0.01	6	60	2	<0.01	3	<1	105	<0.01	<10	10	3	<10	17
LRC06-05 455-460	<0.005	<0.2	0.03	16	<10	<10	<0.5	<2	>25.0	<0.5	1	1	2	0.13	<10	2	0.01	<10	0.05	22	<1	0.01	4	60	2	<0.01	7	<1	117	<0.01	<10	10	2	<10	15
LRC06-05 460-465	<0.005	0.2	0.03	10	<10	<10	<0.5	<2	>25.0	0.8	2	1	3	0.15	<10	1	<0.01	<10	0.06	18	<1	0.01	7	60	3	<0.01	4	<1	115	<0.01	<10	10	3	<10	14
LRC06-05 465-470	<0.005	<0.2	0.03	8	<10	<10	<0.5	<2	>25.0	0.7	1	1	2	0.11	<10	<1	0.01	<10	0.05	18	<1	0.01	4	50	2	<0.01	2	<1	122	<0.01	<10	10	3	<10	19
LRC06-05 470-475	<0.005	<0.2	0.04	23	<10	<10	<0.5	<2	>25.0	0.7	1	1	2	0.16	<10	<1	0.01	<10	0.03	25	<1	0.01	5	70	2	<0.01	4	<1	107	<0.01	<10	10	3	<10	19
LRC06-05 475-480	0.006	<0.2	0.03	5	<10	<10	<0.5	<2	>25.0	0.5	1	1	1	0.06	<10	1	0.01	<10	0.03	21	<1	0.01	5	50	2	<0.01	3	<1	113	<0.01	<10	10	2	<10	10
LRC06-05 480-485	<0.005	<0.2	0.03	10	<10	<10	<0.5	<2	>25.0	0.5	2	1	2	0.15	<10	<1	0.01	<10	0.06	24	<1	0.01	5	60	<2	<0.01	8	<1	102	<0.01	<10	10	2	<10	18
LRC06-05 485-490	<0.005	<0.2	0.02	2	<10	<10	<0.5	<2	>25.0	0.6	1	1	2	0.07	<10	<1	<0.01	<10	0.06	16	<1	0.01	3	70	<2	<0.01	5	<1	103	<0.01	<10	10	2	<10	13
LRC06-05 490-495	<0.005	<0.2	0.02	6	<10	<10	<0.5	<2	>25.0	0.5	1	1	1	0.05	<10	<1	<0.01	<10	0.06	16	<1	0.01	3	60	<2	<0.01	3	<1	87	<0.01	<10	10	2	<10	13
LRC06-05 495-500	<0.005	<0.2	0.02	2	<10	<10	<0.5	<2	>25.0	<0.5	1	1	1	0.08	<10	1	<0.01	<10	0.06	15	<1	0.01	3	60	2	<0.01	3	<1	92	<0.01	<10	10	2	<10	16

VA06087903 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 78
 DATE RECEIVED : 2006-08-22 DATE FINALIZED : 2006-09-23
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE DESCRIPTION	Au	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn
	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm
LRC 06-02 275-280	0.011	0.3	0.28	11	<10	400	<0.5	<2	13.35	1.3	7	18	47	2.57	<10	1	0.1	10	6.37	966	7	0.06	38	710	13	0.72	3	5	1220	0.01	<10	<10	60	<10	182
LRC 06-02 280-285	0.009	0.3	0.58	25	<10	290	0.5	<2	5.37	4	9	31	69	2.89	<10	<1	0.15	10	2.41	563	14	0.04	72	690	12	1.03	6	6	493	0.02	<10	<10	63	<10	426
LRC 06-02 285-290	0.008	0.5	0.39	32	10	160	0.6	<2	3.72	4.8	13	20	79	2.98	<10	<1	0.19	10	1.15	338	28	0.03	105	620	11	1.46	6	9	411	<0.01	<10	<10	74	<10	506
LRC 06-02 290-295	0.005	0.3	0.57	20	<10	270	<0.5	<2	3.45	8	10	48	62	2.37	<10	<1	0.13	<10	1.18	378	19	0.03	97	560	6	0.91	8	6	363	0.03	<10	<10	84	<10	787
LRC 06-02 295-300	0.01	0.3	0.33	44	<10	70	0.5	<2	5.77	16	11	20	96	2.92	<10	<1	0.16	<10	1.31	417	38	0.04	115	650	8	1.76	9	8	764	<0.01	<10	<10	121	<10	1570
LRC 06-02 300-305	0.007	<0.2	0.35	32	<10	90	0.6	<2	7.66	13	10	17	86	2.9	<10	<1	0.17	<10	2.07	457	38	0.05	95	540	8	1.46	7	8	1060	<0.01	<10	<10	124	<10	1270
LRC 06-02 305-310	0.006	0.4	0.29	43	<10	140	0.5	2	6.62	10.1	9	12	69	3.1	<10	<1	0.16	10	1.43	368	32	0.04	83	510	7	1.56	6	8	936	<0.01	10	<10	84	<10	996
LRC 06-02 310-315	0.007	<0.2	0.62	16	<10	260	<0.5	<2	2.51	3.9	9	54	43	2.23	<10	<1	0.12	10	1.21	352	11	0.03	71	520	<2	0.6	4	5	219	0.03	<10	<10	54	<10	397
LRC 06-02 315-320	<0.005	0.3	0.33	41	10	120	0.7	2	4.58	13.3	11	16	84	2.79	<10	<1	0.19	10	1.78	335	30	0.05	113	630	10	1.58	8	8	595	<0.01	<10	<10	81	<10	1280
LRC 06-02 320-325	<0.005	0.2	0.23	11	<10	530	0.5	<2	13.1	3.1	5	18	40	2.75	<10	<1	0.11	10	6.57	919	9	0.07	42	630	6	0.72	2	5	1270	<0.01	<10	<10	68	<10	330
LRC 06-02 325-330	0.009	0.5	0.34	22	10	80	0.7	<2	2.15	4.4	13	16	100	3.42	<10	<1	0.2	10	0.66	298	21	0.05	98	1000	8	2.44	5	8	297	<0.01	<10	<10	55	<10	492
LRC 06-02 330-335	<0.005	0.2	0.5	8	<10	310	<0.5	<2	2.46	2.3	7	31	27	1.99	<10	<1	0.17	10	0.84	305	10	0.04	43	510	2	0.54	<2	4	312	0.02	<10	<10	32	<10	248
LRC 06-02 335-340	<0.005	<0.2	0.35	6	10	370	0.5	<2	4.66	0.6	6	4	23	2.15	<10	<1	0.21	10	0.5	658	6	0.06	23	720	4	0.71	<2	6	608	<0.01	<10	<10	17	<10	121
LRC 06-02 340-345	<0.005	<0.2	0.35	16	10	420	0.6	<2	3.37	2.2	7	5	29	2.19	<10	<1	0.21	10	0.8	313	14	0.06	37	520	4	0.79	2	6	542	<0.01	<10	<10	26	<10	268
LRC 06-02 345-350	<0.005	0.2	0.41	19	10	200	0.5	<2	4.38	4.3	8	15	44	2.57	<10	<1	0.18	10	1.23	413	19	0.06	51	590	4	1.04	3	7	594	0.01	<10	<10	56	<10	456
LRC 06-02 350-355	<0.005	0.3	0.33	18	10	290	0.5	<2	7.28	7.9	7	19	58	2.67	<10	<1	0.15	10	3.21	543	22	0.06	77	450	4	1.07	5	7	770	<0.01	<10	<10	78	<10	801
LRC 06-02 355-360	<0.005	<0.2	0.26	9	<10	550	0.5	<2	12.1	2.7	5	16	42	2.66	<10	<1	0.11	10	5.74	796	8	0.06	36	510	5	0.63	<2	5	1440	<0.01	<10	<10	63	<10	288
LRC 06-02 360-365	<0.005	0.3	0.36	15	10	100	0.7	<2	4.92	2.7	11	22	87	2.99	<10	<1	0.17	<10	2.05	455	13	0.06	82	760	9	1.57	4	7	705	<0.01	<10	<10	55	<10	350
LRC 06-02 365-370	<0.005	0.2	0.29	21	<10	170	0.7	<2	6.53	6.6	8	14	70	2.7	<10	<1	0.15	<10	2.08	628	21	0.06	61	570	6	1.18	4	6	980	<0.01	<10	<10	69	<10	687
LRC 06-02 370-375	0.005	<0.2	0.45	11	<10	300	<0.5	<2	6.53	1.7	6	17	34	2.37	<10	<1	0.14	10	1.57	566	12	0.06	39	570	4	0.93	<2	5	740	0.01	<10	<10	41	<10	229
LRC 06-02 375-380	<0.005	0.2	1.06	16	10	80	0.6	<2	4.97	1.9	12	25	66	3.09	<10	<1	0.21	10	1.15	621	8	0.06	50	840	9	1.44	<2	6	682	0.01	<10	<10	55	<10	270
LRC 06-02 380-385	<0.005	0.3	0.83	12	<10	210	0.5	<2	6.87	1.7	10	25	52	2.64	<10	1	0.17	10	1.39	732	8	0.06	41	670	5	0.98	2	5	957	0.01	<10	<10	54	<10	250
LRC 06-02 385-390	0.007	<0.2	1.33	27	10	160	0.6	<2	4.83	6	15	30	84	3.65	<10	<1	0.25	10	1.16	544	17	0.07	73	960	6	1.94	3	7	709	<0.01	<10	<10	100	<10	670
LRC 06-02 390-395	<0.005	<0.2	1.13	26	<10	150	0.5	<2	4.56	6.7	13	40	81	3.3	<10	<1	0.19	10	1.14	566	20	0.05	75	860	6	1.61	5	6	622	0.01	<10	<10	94	<10	719
LRC 06-02 395-400	0.007	<0.2	1.17	30	<10	160	0.5	<2	4.53	5.9	14	37	73	3.31	<10	<1	0.2	10	1.15	543	17	0.05	82	890	7	1.71	3	7	632	0.01	<10	<10	101	<10	700
LRC 06-02 400-405	0.006	<0.2	1.28	31	10	70	0.6	<2	5.64	6.8	14	32	85	3.35	<10	<1	0.26	10	1.04	570	20	0.06	85	940	6	1.98	5	7	879	<0.01	<10	<10	115	<10	791
LRC 06-02 405-410	<0.005	0.2	1.26	11	10	70	0.6	<2	7.27	4.8	13	24	157	3.18	<10	<1	0.26	10	1.02	677	16	0.07	68	930	9	1.74	2	6	1130	<0.01	<10	<10	94	<10	613
LRC 06-02 410-415	0.006	0.3	1.36	11	10	230	0.6	<2	4.14	1.8	12	35	86	3.06	<10	<1	0.27	10	1.15	523	7	0.06	49	1120	8	0.99	<2	5	542	0.02	<10	<10	63	<10	245
LRC 06-02 415-420	0.005	0.5	1.26	11	10	120	0.7	<2	4.59	1.4	11	26	95	2.95	<10	<1	0.26	10	0.98	547	6	0.06	40	1140	9	1.17	<2	5	605	0.01	<10	<10	53	<10	211
LRC 06-02 420-425	<0.005	0.2	1.18	18	10	60	0.7	<2	5.67	2.3	12	19	78	2.95	<10	<1	0.3	10	0.79	555	12	0.07	49	1050	10	1.67	<2	5	727	<0.01	<10	<10	56	<10	278
LRC 06-02 425-430	<0.005	<0.2	1.39	17	10	120	0.7	<2	6	3.7	14	28	82	3.45	<10	<1	0.28	10	1.2	648	12	0.08	56	960	8	1.74	2	7	733	<0.01	<10	<10	89	<10	420
LRC 06-02 430-435	0.007	0.3	1.68	19	10	130	0.7	<2	4.84	4	15	37	79	3.79	10	<1	0.3	10	1.45	584	10	0.08	58	910	8	1.65	2	8	575	0.01	<10	<10	107	<10	448
LRC 06-02 435-440	<0.005	0.3	1.79	17	10	140	0.5	2	5.16	3.2	16	42	73	3.76	<10	<1	0.25	10	1.7	655	6	0.07	47	870	5	1.36	3	9	579	<0.01	<10	<10	108	<10	375
LRC 06-02 440-445	<0.005	<0.2	1.71	11	10	110	0.6	<2	5.15	3.8	15	36	74	3.74	<10	<1	0.26	10	1.56	622	9	0.08	52	820	4	1.53	2	8	594	<0.01	<10	<10	113	<10	451
LRC 06-02 445-450	0.006	<0.2	1.63	12	10	110	0.6	<2	5.84	3.5	14	36	79	3.82	10	<1	0.27	10	1.57	639	10	0.08	60	920	9	1.66	4	8	699	0.01	<10	<10	102	<10	404
LRC 06-02 450-455	0.005	0.2	1.69	11	10	140	0.6	<2	5.27	3.3	15	41	75	3.85	<10	<1	0.24	10	1.62	605	9	0.08	58	840	6	1.49	<2	8	616	0.01	<10	<10	108	<10	397
LRC 06-02 455-460	<0.005	<0.2	1.88	11	10	280	0.5	<2	4.72	2.1	16	47	68	3.82	<10	<1	0.26	10	1.77	657	5	0.08	46	920	5	1.23	2	9	505	0.01	<10	<10	97	<10	273
LRC 06-02 460-465	0.008	<0.2	2.2	25	10	90	0.6	<2	4.24	4	19	52	99	4.71	10	<1	0.25	10	2	530	8	0.08	77	980	6	1.79	3	10	497	0.01	<10	<10	155	<10	500
LRC 06-02 465-470	0.006	<0.2	2.15	16	10																														

VA06091461 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 112
 DATE RECEIVED : 2006-08-24 DATE FINALIZED : 2006-10-03
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE DESCRIPTION	Au	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn		
	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
LRC 06-08 155-160	<0.005	<0.2	1.08	10	<10	70	<0.5	<2	5.86	<0.5	42	132	208	9.77	<10	4	0.02	<10	0.3	1130	4	<0.01	132	390	<2	0.02	12	24	43	0.03	<10	<10	237	<10	124		
LRC 06-08 160-165	<0.005	<0.2	0.96	4	<10	70	<0.5	<2	8.93	<0.5	30	84	206	7.32	<10	4	0.05	<10	1.05	1160	2	0.01	76	390	<2	0.02	7	16	81	0.03	<10	<10	183	<10	87		
LRC 06-08 165-170	<0.005	<0.2	1.06	5	<10	60	<0.5	<2	8.2	<0.5	24	86	130	7.7	<10	<1	0.04	<10	1.91	1020	<1	0.01	58	370	<2	0.02	5	19	97	0.05	<10	<10	201	<10	73		
LRC 06-08 170-175	<0.005	<0.2	1.17	4	<10	70	<0.5	<2	6.59	<0.5	31	89	160	7.73	<10	5	0.06	<10	1.01	880	1	0.01	93	470	<2	0.02	6	19	77	0.06	<10	<10	211	<10	90		
LRC 06-08 175-180	0.009	<0.2	1.23	4	<10	40	<0.5	<2	7.64	<0.5	37	106	201	9.25	<10	<1	0.07	<10	1.69	986	<1	0.01	110	450	<2	0.02	3	21	115	0.07	<10	<10	233	<10	104		
LRC 06-08 180-185	<0.005	<0.2	0.77	<2	<10	60	<0.5	<2	8.53	<0.5	26	88	361	7.95	<10	1	0.05	<10	2.59	1080	<1	0.01	65	360	<2	0.02	7	19	107	0.06	<10	<10	200	<10	78		
LRC 06-08 185-190	<0.005	<0.2	0.73	2	<10	130	<0.5	<2	6.39	<0.5	24	90	230	6.6	<10	<1	0.08	<10	1.56	894	<1	0.01	75	370	<2	0.02	3	20	78	0.03	<10	<10	194	<10	74		
LRC 06-08 190-195	0.005	<0.2	0.98	7	<10	100	<0.5	<2	5.91	<0.5	35	115	207	7.65	<10	<1	0.1	<10	1.38	1010	<1	0.01	115	380	<2	0.02	5	22	81	0.04	<10	<10	212	<10	95		
LRC 06-08 195-200	0.005	<0.2	1.1	2	<10	50	<0.5	<2	5.94	<0.5	43	103	292	9	<10	<1	0.1	<10	2.23	1190	<1	0.01	126	380	<2	0.02	4	18	84	0.04	<10	<10	185	<10	124		
LRC 06-08 200-205	<0.005	<0.2	0.94	3	<10	50	<0.5	<2	6.75	<0.5	42	99	199	9.1	<10	<1	0.08	<10	1.74	1010	<1	0.01	131	390	<2	0.02	6	19	101	0.05	<10	<10	193	<10	114		
LRC 06-08 205-210	<0.005	<0.2	1.05	2	<10	50	<0.5	<2	5.98	<0.5	46	110	258	9.03	<10	<1	0.07	<10	2.24	859	<1	0.01	147	370	<2	0.02	8	22	111	0.06	<10	<10	216	<10	131		
LRC 06-08 210-215	<0.005	<0.2	1.57	4	<10	60	<0.5	2	6.15	<0.5	43	121	217	9.3	<10	<1	0.07	<10	1.97	888	<1	0.01	133	380	<2	0.02	13	23	94	0.08	<10	<10	240	<10	119		
LRC 06-08 215-220	0.005	<0.2	1.53	<2	<10	60	<0.5	<2	4.36	<0.5	46	108	140	8.79	<10	<1	0.05	<10	2.19	971	<1	0.01	138	390	<2	0.02	9	25	81	0.04	<10	<10	228	<10	130		
LRC 06-08 220-225	<0.005	<0.2	1.77	4	<10	60	<0.5	<2	5.06	<0.5	42	95	126	8.87	<10	<1	0.04	<10	2.75	963	1	0.01	112	370	<2	0.02	9	25	104	0.06	<10	<10	239	<10	119		
LRC 06-08 225-230	<0.005	<0.2	2.1	<2	<10	50	<0.5	<2	5.5	<0.5	48	92	150	9.54	<10	<1	0.05	<10	2.84	837	1	0.01	124	410	<2	0.03	11	24	117	0.07	<10	<10	249	<10	128		
LRC 06-08 230-235	<0.005	<0.2	2.19	5	<10	40	<0.5	<2	6.96	<0.5	38	87	219	9.03	10	2	0.09	<10	3.06	961	<1	0.01	113	350	<2	0.04	13	21	140	0.06	<10	<10	202	<10	118		
LRC 06-08 230-240	<0.005	0.3	1.79	3	<10	60	<0.5	<2	5.63	<0.5	37	87	200	7.82	10	5	0.14	<10	2.25	887	<1	0.01	103	380	2	0.01	17	18	100	0.05	<10	<10	160	<10	93		
LRC 06-08 240-245	<0.005	<0.2	1.77	2	10	50	<0.5	<2	6.18	<0.5	36	71	363	8.76	10	5	0.28	<10	2.6	904	1	0.01	93	380	<2	0.02	15	17	111	0.05	<10	<10	151	<10	96		
LRC 06-08 245-250	<0.005	0.2	1.53	14	10	40	<0.5	<2	4.11	<0.5	36	58	382	9.53	<10	13	0.4	<10	2.19	798	1	0.02	113	310	<2	0.24	40	16	68	0.04	<10	<10	108	<10	97		
LRC 06-08 250-255	<0.005	0.2	1.53	298	10	50	<0.5	<2	4.13	<0.5	42	50	468	9.88	<10	87	0.42	<10	2.41	879	<1	0.02	128	270	<2	0.82	152	17	75	0.01	<10	<10	94	<10	114		
LRC 06-08 255-260	0.141	<0.2	1.93	1390	20	40	<0.5	<2	6.77	<0.5	49	49	214	7.94	<10	25	0.39	<10	2.91	1080	<1	0.02	131	350	<2	2.48	100	16	117	<0.01	<10	10	99	<10	105		
LRC 06-08 260-265	0.192	<0.2	1.57	2250	20	40	<0.5	<2	6.93	<0.5	52	41	195	8.93	<10	19	0.42	<10	2.06	1050	<1	0.02	128	400	<2	4.16	94	16	95	<0.01	<10	<10	88	<10	117		
LRC 06-08 265-270	0.047	<0.2	1.41	1230	20	50	<0.5	<2	2.52	<0.5	39	41	120	12.3	<10	10	0.57	<10	0.58	563	<1	0.01	123	160	<2	3.28	62	15	39	0.01	<10	<10	74	<10	110		
LRC 06-08 270-275	0.035	<0.2	1.02	1100	10	70	<0.5	<2	11.75	<0.5	33	30	510	8.43	<10	98	0.42	<10	0.52	594	<1	0.01	103	260	<2	2.28	226	11	167	0.01	<10	10	55	<10	117		
LRC 06-08 275-280	0.018	<0.2	0.61	454	10	20	<0.5	<2	>25.0	<0.5	12	15	74	3.53	<10	9	0.24	<10	0.39	401	<1	0.01	38	90	<2	1.1	41	5	215	0.01	<10	10	28	<10	40		
LRC 06-08 280-285	0.009	<0.2	0.35	273	<10	10	<0.5	<2	>25.0	<0.5	9	9	48	2.27	<10	5	0.15	<10	0.65	374	<1	0.01	26	90	<2	0.6	24	3	193	<0.01	<10	10	18	<10	32		
LRC 06-08 285-290	<0.005	0.2	0.13	59	<10	10	<0.5	<2	>25.0	<0.5	3	6	21	0.62	<10	3	0.04	<10	0.7	362	<1	0.01	9	50	2	<0.01	13	1	448	<0.01	<10	10	10	<10	16		
LRC 06-08 290-295	<0.005	<0.2	0.04	24	<10	10	<0.5	<2	>25.0	0.5	2	5	11	0.22	<10	<1	0.01	<10	0.58	175	<1	0.01	4	160	<2	<0.01	5	<1	274	<0.01	<10	10	4	<10	12		
LRC 06-08 295-300	<0.005	0.2	0.05	31	<10	10	<0.5	<2	>25.0	0.5	2	3	24	0.31	<10	2	0.02	<10	6.17	273	<1	0.02	4	70	2	<0.01	10	<1	173	<0.01	<10	10	3	<10	23		
LRC 06-08 300-305	<0.005	<0.2	0.04	20	<10	10	<0.5	<2	>25.0	<0.5	2	2	9	0.22	<10	1	0.01	<10	0.25	117	<1	0.01	4	60	3	<0.01	4	<1	216	<0.01	<10	10	3	<10	12		
LRC 06-08 305-310	<0.005	0.2	0.03	17	<10	10	<0.5	<2	>25.0	<0.5	2	2	32	0.16	<10	5	0.01	<10	0.34	101	<1	0.01	2	70	<2	<0.01	14	<1	190	<0.01	<10	10	3	<10	11		
LRC 06-08 310-315	<0.005	<0.2	0.04	10	<10	10	<0.5	<2	>25.0	0.7	2	2	7	0.17	<10	1	0.01	<10	0.29	94	<1	0.01	4	120	<2	<0.01	4	<1	187	<0.01	<10	10	4	<10	11		
LRC 06-08 315-320	<0.005	<0.2	0.02	11	<10	10	<0.5	<2	>25.0	<0.5	2	1	10	0.13	<10	1	0.01	<10	0.31	72	<1	0.01	3	40	2	<0.01	4	<1	174	<0.01	<10	10	2	<10	9		
LRC 06-08 320-325	<0.005	<0.2	0.02	8	<10	10	<0.5	<2	>25.0	0.5	1	1	5	0.11	<10	1	<0.01	<10	0.34	67	<1	0.01	2	30	2	<0.01	3	<1	173	<0.01	<10	10	2	<10	9		
LRC 06-08 325-330	<0.005	0.2	0.1	23	<10	20	<0.5	2	>25.0	0.6	2	5	15	0.42	<10	2	0.01	<10	0.33	102	<1	0.01	8	70	<2	<0.01	4	1	178	0.01	<10	10	8	<10	15		
LRC 06-08 330-335	<0.005	<0.2	0.03	15	<10	10	<0.5	<2	>25.0	0.6	2	2	6	0.16	<10	1	0.01	<10	0.34	65	<1	0.01	4	40	<2	<0.01	3	<1	207	<0.01	<10	10	3	<10	15		
LRC 06-08 335-340	<0.005	<0.2	0.03	11	<10	10	<0.5	<2	>25.0	<0.5	2	1	5	0.13	<10	1	0.01	<10	0.3	63	<1	0.01	3	40	<2	<0.01	4	<1	170	<0.01	<10	10	3	<10	13		
LRC 06-08 340-345	<0.																																				

VA06091462 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 80
 DATE RECEIVED : 2006-08-25 DATE FINALIZED : 2006-09-27
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE DESCRIPTION	Au	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn	
	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
LRC 06-11 25-30	<0.005	<0.2	0.14	19	<10	20	<0.5	<2	>25.0	3	1	5	6	0.26	<10	7	0.02	<10	0.08	117	<1	<0.01	5	80	<2	<0.01	18	1	417	<0.01	<10	10	3	<10	40	
LRC 06-11 30-35	<0.005	<0.2	0.14	16	<10	20	<0.5	<2	>25.0	1.7	1	5	6	0.24	<10	5	0.02	<10	0.09	92	<1	<0.01	5	80	<2	<0.01	17	1	365	<0.01	<10	10	3	<10	37	
LRC 06-11 35-40	<0.005	<0.2	0.19	24	<10	30	<0.5	<2	>25.0	2.1	1	6	8	0.32	<10	6	0.03	<10	0.11	89	<1	<0.01	6	120	2	<0.01	11	1	316	<0.01	<10	10	4	<10	42	
LRC 06-11 40-45	<0.005	<0.2	0.17	29	<10	20	<0.5	<2	>25.0	3	1	6	8	0.35	<10	6	0.03	<10	0.1	87	<1	<0.01	7	110	2	<0.01	10	1	292	<0.01	<10	10	4	<10	48	
LRC 06-11 45-50	<0.005	<0.2	0.11	27	<10	20	<0.5	<2	>25.0	3.8	1	4	5	0.29	<10	7	0.02	<10	0.07	71	<1	<0.01	6	120	<2	<0.01	11	<1	172	<0.01	<10	10	3	<10	43	
LRC 06-11 50-55	<0.005	<0.2	0.11	18	<10	20	<0.5	<2	>25.0	2	1	4	4	0.23	<10	5	0.02	<10	0.07	66	<1	<0.01	4	140	2	<0.01	10	<1	148	<0.01	<10	10	3	<10	40	
LRC 06-11 55-60	<0.005	<0.2	0.06	10	<10	10	<0.5	<2	>25.0	1.2	<1	2	2	0.12	<10	3	0.01	<10	0.06	56	<1	<0.01	2	90	<2	<0.01	6	<1	129	<0.01	<10	10	2	<10	27	
LRC 06-11 60-65	<0.005	<0.2	0.11	18	<10	20	<0.5	<2	>25.0	2	1	4	4	0.23	<10	4	0.02	<10	0.08	81	<1	<0.01	5	100	<2	<0.01	7	<1	142	<0.01	<10	10	3	<10	38	
LRC 06-11 65-70	<0.005	<0.2	0.1	16	<10	20	<0.5	<2	>25.0	2.7	1	4	4	0.2	<10	5	0.02	<10	0.09	91	<1	0.01	4	120	<2	<0.01	13	1	158	<0.01	<10	<10	5	<10	34	
LRC 06-11 70-75	<0.005	<0.2	0.11	20	<10	20	<0.5	<2	>25.0	2.6	2	4	5	0.26	<10	5	0.02	<10	0.09	87	<1	0.01	4	170	3	<0.01	10	1	158	<0.01	<10	<10	6	<10	43	
LRC 06-11 75-80	<0.005	<0.2	0.07	17	<10	10	<0.5	<2	>25.0	1.8	1	3	3	0.18	<10	4	0.01	<10	0.07	70	<1	0.01	2	120	<2	<0.01	6	<1	146	<0.01	<10	<10	4	<10	32	
LRC 06-11 80-85	<0.005	<0.2	0.06	21	<10	10	<0.5	<2	>25.0	1.7	1	3	3	0.22	<10	4	0.01	<10	0.08	66	<1	0.01	2	120	2	<0.01	7	<1	141	<0.01	<10	<10	4	<10	33	
LRC 06-11 85-90	<0.005	<0.2	0.05	23	<10	10	<0.5	<2	>25.0	1.6	<1	2	3	0.15	<10	3	0.01	<10	0.06	62	<1	0.01	2	100	<2	<0.01	7	<1	148	<0.01	<10	<10	2	<10	23	
LRC 06-11 90-95	<0.005	<0.2	0.05	28	<10	10	<0.5	<2	>25.0	1.8	<1	3	3	0.21	<10	6	0.01	<10	0.07	84	<1	0.02	2	100	<2	<0.01	8	1	156	<0.01	<10	<10	3	<10	31	
LRC 06-11 95-100	<0.005	<0.2	0.05	47	<10	10	<0.5	<2	>25.0	2.1	<1	4	4	0.6	<10	12	0.01	<10	0.06	121	<1	0.01	4	100	<2	<0.01	18	<1	119	<0.01	<10	<10	3	<10	44	
LRC 06-11 100-105	<0.005	<0.2	0.03	24	<10	10	<0.5	<2	>25.0	1.9	<1	2	2	0.19	<10	9	<0.01	<10	0.06	89	<1	0.02	2	90	<2	<0.01	9	<1	118	<0.01	<10	<10	2	<10	30	
LRC 06-11 105-110	<0.005	<0.2	0.03	17	<10	10	<0.5	<2	>25.0	1.9	<1	2	2	0.12	<10	5	<0.01	<10	0.07	81	<1	0.02	1	110	<2	<0.01	5	<1	158	<0.01	<10	<10	2	<10	25	
LRC 06-11 110-115	<0.005	<0.2	0.03	13	<10	10	<0.5	<2	>25.0	1.9	<1	2	2	0.08	<10	3	<0.01	<10	0.05	84	<1	0.01	1	110	<2	<0.01	6	<1	113	<0.01	<10	<10	1	<10	22	
LRC 06-11 115-120	<0.005	<0.2	0.03	19	<10	10	<0.5	<2	>25.0	2.6	<1	2	2	0.09	<10	4	<0.01	<10	0.06	63	<1	0.01	1	100	<2	<0.01	4	<1	137	<0.01	<10	<10	1	<10	22	
LRC 06-11 120-125	<0.005	<0.2	0.06	15	<10	10	<0.5	<2	>25.0	1.4	<1	2	3	0.13	<10	4	0.01	<10	0.07	88	<1	0.01	3	100	<2	<0.01	10	<1	110	<0.01	<10	<10	2	<10	29	
LRC 06-11 125-130	<0.005	<0.2	0.03	14	<10	10	<0.5	<2	>25.0	1.5	<1	2	2	0.1	<10	6	<0.01	<10	0.07	92	<1	0.01	1	80	<2	<0.01	5	<1	145	<0.01	<10	<10	2	<10	21	
LRC 06-11 130-135	0.015	<0.2	0.03	12	<10	10	<0.5	<2	>25.0	1.5	<1	3	6	0.34	<10	9	0.01	<10	0.08	132	<1	0.01	4	160	3	<0.01	11	1	192	<0.01	<10	<10	2	<10	73	
LRC 06-11 135-140	0.02	0.4	0.11	84	<10	10	<0.5	<2	>25.0	2.2	14	12	42	1.3	<10	17	0.02	<10	0.09	783	<1	0.01	97	1010	23	<0.01	83	1	179	<0.01	<10	<10	10	<10	412	
LRC 06-11 140-145	0.005	0.2	0.06	31	<10	20	<0.5	<2	>25.0	1.7	3	4	18	0.91	<10	20	0.01	<10	0.08	475	<1	0.02	20	430	14	<0.01	39	1	274	<0.01	<10	<10	4	<10	162	
LRC 06-11 145-150	<0.005	<0.2	0.03	11	<10	10	<0.5	<2	>25.0	1.8	<1	3	4	0.09	<10	6	0.01	<10	0.07	109	<1	0.01	1	110	<2	<0.01	7	<1	250	<0.01	<10	<10	1	<10	44	
LRC 06-11 150-155	<0.005	<0.2	0.04	13	<10	10	<0.5	<2	>25.0	1.7	<1	3	4	0.17	<10	3	0.01	<10	0.07	99	<1	0.02	3	100	<2	<0.01	15	1	294	<0.01	<10	<10	2	<10	53	
LRC 06-11 155-160	<0.005	<0.2	0.03	12	<10	10	<0.5	<2	>25.0	1.7	<1	3	2	0.1	<10	2	<0.01	<10	0.05	69	<1	0.02	3	80	<2	<0.01	10	<1	380	<0.01	<10	<10	1	<10	23	
LRC 06-11 160-165	<0.005	<0.2	0.07	102	<10	10	<0.5	<2	>25.0	1.6	<1	8	7	0.55	<10	25	0.01	<10	0.06	65	<1	0.02	16	240	<2	<0.01	108	1	319	<0.01	<10	<10	4	<10	74	
LRC 06-11 165-170	0.005	<0.2	0.07	46	<10	10	<0.5	<2	>25.0	1.4	<1	9	4	0.3	<10	4	0.01	<10	0.07	70	<1	0.01	8	180	<2	<0.01	48	1	375	<0.01	<10	<10	3	<10	43	
LRC 06-11 170-175	<0.005	0.2	0.07	13	<10	10	<0.5	<2	>25.0	3.1	<1	8	4	0.15	<10	5	0.02	<10	0.07	53	<1	0.01	4	80	3	<0.01	6	1	504	<0.01	<10	<10	3	<10	26	
LRC 06-11 175-180	<0.005	<0.2	0.05	8	<10	10	<0.5	<2	>25.0	1.8	<1	5	3	0.15	<10	3	0.01	<10	0.08	54	<1	0.01	2	70	<2	<0.01	7	1	378	<0.01	<10	<10	3	<10	23	
LRC 06-11 180-185	<0.005	<0.2	0.04	12	<10	10	<0.5	<2	>25.0	0.7	<1	4	3	0.11	<10	4	0.01	<10	0.09	43	<1	0.01	2	50	<2	<0.01	4	<1	463	<0.01	<10	<10	2	<10	21	
LRC 06-11 185-190	<0.005	<0.2	0.03	11	<10	10	<0.5	<2	>25.0	1.4	<1	4	3	0.11	<10	3	0.01	<10	0.07	63	<1	0.01	4	70	<2	<0.01	6	<1	345	<0.01	<10	<10	2	<10	20	
LRC 06-11 190-195	<0.005	<0.2	0.04	14	<10	10	<0.5	<2	>25.0	0.8	<1	3	2	0.12	<10	6	0.01	<10	0.08	55	<1	0.02	<1	60	<2	<0.01	5	<1	443	<0.01	<10	<10	2	<10	18	
LRC 06-11 195-200	<0.005	<0.2	0.03	6	<10	10	<0.5	<2	>25.0	0.8	<1	3	2	0.07	<10	7	<0.01	<10	0.06	47	<1	0.02	1	50	<2	<0.01	3	<1	383	<0.01	<10	<10	2	<10	14	
LRC 06-11 200-205	<0.005	<0.2	0.04	6	<10	10	<0.5	<2	>25.0	1	<1	3	6	0.1	<10	4	0.01	<10	0.05	64	<1	0.02	3	70	6	<0.01	3	<1	343	<0.01	<10	<10	2	<10	25	
LRC 06-11 205-210	<0.005	<0.2	0.04	18	<10	10	<0.5	<2	>25.0	0.9	<1	3	4	0.16	<10	4	0.01	<10	0.06	111	<1	0.02	2	80	2	<0.01	6	<1	154	<0.01	<10	<10	4	<10	22	
LRC 06-11 210-215	<0.005	<0.2	0.04	9	<10	10	<0.5	<2	>2																											

VA06091589 - Finalized
CLIENT : "SHK - Alpha Gold Corp."
of SAMPLES : 99
DATE RECEIVED : 2006-08-28 DATE FINALIZED : 2006-10-03
PROJECT : "Lust Dust"
CERTIFICATE COMMENTS : ""
PO NUMBER : ""

SAMPLE DESCRIPTION	Au ppm	Ag ppm	Al %	As ppm	B ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
LRC 06-10 20-25	<0.005	<0.2	0.03	5	<10	10	<0.5	<2	>25.0	0.6	1	4	2	0.08	<10	2	<0.01	<10	0.09	51	<1	0.01	2	60	<2	<0.01	<2	<1	143	<0.01	<10	<10	1	<10	10
LRC 06-10 25-30	0.005	<0.2	0.03	<2	<10	10	<0.5	<2	>25.0	0.7	1	4	1	0.07	<10	2	0.01	<10	0.07	51	<1	0.01	<1	50	2	<0.01	<2	<1	138	<0.01	<10	<10	1	<10	10
LRC 06-10 30-35	0.005	<0.2	0.1	8	<10	20	<0.5	<2	>25.0	0.9	1	3	2	0.09	<10	4	0.03	<10	0.08	65	<1	0.01	2	100	2	<0.01	3	1	170	<0.01	<10	<10	1	<10	13
LRC 06-10 35-40	0.009	<0.2	0.04	5	<10	10	<0.5	<2	>25.0	0.8	1	3	1	0.06	<10	3	0.01	<10	0.07	64	<1	0.01	2	70	2	<0.01	3	<1	135	<0.01	<10	<10	<1	<10	8
LRC 06-10 40-45	<0.005	<0.2	0.05	17	<10	20	<0.5	<2	>25.0	1.4	1	3	3	0.2	<10	20	0.01	<10	0.07	112	<1	0.01	3	100	3	<0.01	7	1	142	<0.01	<10	<10	1	<10	28
LRC 06-10 45-50	<0.005	<0.2	0.08	40	<10	20	<0.5	<2	>25.0	1.7	2	6	6	0.45	<10	29	0.01	<10	0.07	153	<1	0.01	9	130	4	<0.01	23	1	139	<0.01	<10	<10	4	<10	64
LRC 06-10 50-55	<0.005	<0.2	0.08	40	<10	20	<0.5	<2	>25.0	1.8	3	6	9	0.49	<10	23	0.01	<10	0.07	163	<1	0.01	12	140	5	<0.01	16	1	146	<0.01	<10	<10	5	<10	90
LRC 06-10 55-60	<0.005	<0.2	0.09	21	<10	20	<0.5	<2	>25.0	1.4	2	4	6	0.38	<10	14	0.01	<10	0.07	155	<1	0.01	7	120	3	<0.01	8	1	166	<0.01	<10	<10	4	<10	49
LRC 06-10 60-65	0.006	0.5	0.72	111	<10	90	<0.5	<2	21.8	2.3	7	19	36	2.11	<10	21	0.07	<10	0.36	465	1	0.01	29	460	10	<0.01	30	3	107	0.02	<10	<10	21	<10	173
LRC 06-10 65-70	0.009	0.2	0.7	95	<10	90	<0.5	<2	>25.0	1.8	6	17	33	1.63	<10	19	0.07	<10	0.34	365	1	0.02	27	380	9	<0.01	24	3	152	0.02	<10	<10	21	<10	124
LRC 06-10 70-75	0.007	<0.2	0.53	61	<10	60	<0.5	<2	>25.0	1.4	5	14	23	1.1	<10	15	0.05	<10	0.23	186	1	0.02	23	360	4	<0.01	27	2	163	0.02	<10	<10	16	<10	74
LRC 06-10 75-80	<0.005	<0.2	0.11	15	<10	20	<0.5	<2	>25.0	0.9	1	3	5	0.22	<10	8	0.01	<10	0.1	93	<1	0.02	5	150	<2	<0.01	6	1	201	<0.01	<10	<10	6	<10	23
LRC 06-10 80-85	<0.005	<0.2	0.33	37	<10	50	<0.5	<2	>25.0	0.9	3	9	15	0.6	<10	14	0.04	<10	0.14	123	<1	0.02	15	240	4	<0.01	13	2	178	0.01	<10	<10	11	<10	48
LRC 06-10 85-90	0.005	<0.2	0.45	44	<10	60	<0.5	<2	>25.0	0.8	3	12	18	0.72	<10	11	0.06	<10	0.16	106	<1	0.02	18	300	3	<0.01	18	2	176	0.01	<10	<10	13	<10	57
LRC 06-10 90-95	<0.005	<0.2	0.03	4	<10	10	<0.5	<2	>25.0	0.6	1	2	1	0.07	<10	2	<0.01	<10	0.07	46	<1	0.02	2	380	<2	<0.01	<2	<1	168	<0.01	<10	<10	3	<10	10
LRC 06-10 95-100	<0.005	<0.2	0.03	4	<10	10	<0.5	<2	>25.0	0.7	1	2	1	0.09	<10	2	0.01	<10	0.09	34	<1	0.02	4	150	<2	<0.01	3	<1	156	<0.01	<10	<10	3	<10	11
LRC 06-10 100-105	0.012	<0.2	0.19	17	<10	10	<0.5	<2	>25.0	1	1	6	3	0.21	<10	7	0.06	<10	0.07	40	<1	0.02	7	100	2	<0.01	5	1	178	<0.01	<10	<10	5	<10	23
LRC 06-10 105-110	<0.005	<0.2	0.03	7	<10	10	<0.5	<2	>25.0	0.7	<1	2	2	0.07	<10	2	<0.01	<10	0.07	24	<1	0.02	2	50	<2	<0.01	2	<1	153	<0.01	<10	<10	3	<10	8
LRC 06-10 110-115	0.005	<0.2	0.09	25	<10	10	<0.5	<2	>25.0	1	1	4	5	0.29	<10	7	0.02	<10	0.09	44	<1	0.01	4	110	2	<0.01	5	1	162	<0.01	<10	<10	5	<10	24
LRC 06-10 115-120	<0.005	<0.2	0.12	23	<10	20	<0.5	<2	>25.0	1	1	5	4	0.27	<10	8	0.03	<10	0.1	45	<1	0.02	4	100	<2	<0.01	7	1	176	<0.01	<10	<10	6	<10	23
LRC 06-10 120-125	<0.005	<0.2	0.07	21	<10	20	<0.5	<2	>25.0	2	1	4	4	0.24	<10	6	0.01	<10	0.09	56	<1	0.02	3	120	<2	<0.01	8	1	219	<0.01	<10	<10	6	<10	21
LRC 06-10 125-130	<0.005	<0.2	0.03	11	<10	10	<0.5	<2	>25.0	0.7	<1	3	2	0.11	<10	4	0.01	<10	0.09	51	<1	0.02	2	90	<2	<0.01	3	1	205	<0.01	<10	<10	4	<10	10
LRC 06-10 130-135	<0.005	<0.2	0.04	10	<10	10	<0.5	<2	>25.0	0.7	<1	2	2	0.14	<10	5	0.01	<10	0.09	54	<1	0.02	2	120	<2	<0.01	4	<1	213	<0.01	<10	<10	4	<10	11
LRC 06-10 135-140	<0.005	<0.2	0.03	8	<10	10	<0.5	<2	>25.0	0.9	1	2	6	0.13	<10	3	0.01	<10	0.09	50	<1	0.02	2	80	6	<0.01	4	<1	216	<0.01	<10	<10	4	<10	19
LRC 06-10 140-145	<0.005	<0.2	0.03	10	<10	10	<0.5	<2	>25.0	1	1	2	3	0.11	<10	6	<0.01	<10	0.09	66	<1	0.02	2	70	2	<0.01	<2	<1	225	<0.01	<10	<10	4	<10	14
LRC 06-10 145-150	<0.005	<0.2	0.04	9	<10	10	<0.5	<2	>25.0	1.1	<1	2	2	0.13	<10	6	0.01	<10	0.08	80	<1	0.02	2	130	<2	<0.01	2	<1	184	<0.01	<10	<10	4	<10	16
LRC 06-10 150-155	<0.005	<0.2	0.13	67	<10	20	<0.5	<2	>25.0	1.4	2	6	6	0.8	<10	15	0.02	<10	0.08	164	<1	0.02	7	270	2	<0.01	22	1	155	<0.01	<10	<10	9	<10	44
LRC 06-10 155-160	0.007	<0.2	0.53	200	<10	60	<0.5	<2	>25.0	2.2	6	18	23	2.07	<10	38	0.07	<10	0.15	208	1	0.02	26	770	7	<0.01	73	2	133	0.01	<10	<10	22	<10	180
LRC 06-10 160-165	0.005	<0.2	0.05	27	<10	10	<0.5	<2	>25.0	1.1	1	3	3	0.34	<10	6	0.01	<10	0.08	81	<1	0.02	3	120	<2	<0.01	10	<1	210	<0.01	<10	<10	5	<10	25
LRC 06-10 165-170	0.01	<0.2	0.06	19	<10	10	<0.5	<2	>25.0	1	1	3	3	0.26	<10	6	0.01	<10	0.08	95	<1	0.02	3	140	<2	<0.01	11	1	208	<0.01	<10	<10	5	<10	23
LRC 06-10 170-175	<0.005	<0.2	0.06	22	<10	10	<0.5	<2	>25.0	1	1	3	3	0.27	<10	6	0.01	<10	0.08	109	<1	0.02	3	150	<2	<0.01	12	1	189	<0.01	<10	<10	5	<10	24
LRC 06-10 175-180	<0.005	<0.2	0.04	14	<10	10	<0.5	<2	>25.0	0.7	1	3	3	0.16	<10	3	0.01	<10	0.07	102	<1	0.02	2	90	<2	<0.01	6	<1	189	<0.01	<10	<10	4	<10	17
LRC 06-10 180-185	<0.005	<0.2	0.04	13	<10	10	<0.5	<2	>25.0	0.7	<1	3	2	0.17	<10	3	0.01	<10	0.08	89	<1	0.02	2	90	<2	<0.01	6	<1	201	<0.01	<10	<10	4	<10	15
LRC 06-10 185-190	<0.005	<0.2	0.04	14	<10	10	<0.5	<2	>25.0	0.6	<1	2	2	0.16	<10	3	0.01	<10	0.08	72	<1	0.02	2	90	<2	<0.01	4	<1	161	<0.01	<10	<10	4	<10	14
LRC 06-10 190-195	<0.005	<0.2	0.06	16	<10	10	<0.5	<2	>25.0	0.8	1	3	3	0.25	<10	5	0.01	<10	0.08	80	<1	0.02	3	170	<2	<0.01	6	<1	177	<0.01	<10	<10	5	<10	19
LRC 06-10 195-200	<0.005	<0.2	0.08	18	<10	20	<0.5	<2	>25.0	0.8	1	3	4	0.33	<10	4	0.01	<10	0.09	98	<1	0.02	3	110	<2	<0.01	8	1	163	<0.01	<10	<10	6	<10	22
LRC 06-10 200-205	<0.005	<0.2	0.07	17	<10	20	<0.5	<2	>25.0	0.8	1	3	3	0.28	<10	4	0.01	<10	0.08	153	<1	0.02	3	80	<2	<0.01	13	1	119	<0.01	<10	<10	5	<10	21
LRC 06-10 205-210	<0.005	<0.2	0.08	18	<10	20	<0.5	<2	>25.0	0.9	1	4	4	0.34	<10	5	0.01	<10	0.09	129	<1	0.02	4	110	2	<0.01	9	1	117	<0.01	<10	<10	6	<10	28
LRC 06-10 210-215	<0.005	<0.2	0.06	15	<10	10	<0.5	<2	>25.0	0.6	1	3	2	0.24	<10																				

VA06091589 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 99
 DATE RECEIVED : 2006-08-28 DATE FINALIZED : 2006-10-03
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE DESCRIPTION	Au	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn
	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	
LRC 06-12 420-425	<0.005	0.2	0.47	16	<10	190	0.5	<2	3.73	1.9	17	31	84	4.71	<10	1	0.2	<10	2.12	531	6	0.03	66	570	9	1.75	<2	10	167	<0.01	<10	<10	81	<10	246
LRC 06-12 425-430	<0.005	<0.2	0.36	8	<10	220	<0.5	<2	7.05	0.8	10	17	43	3.48	<10	1	0.17	<10	1.97	633	3	0.02	36	400	6	0.77	<2	9	297	<0.01	<10	<10	44	<10	144
LRC 06-12 430-435	<0.005	<0.2	0.39	9	<10	290	0.5	2	4.89	0.8	13	18	60	4.44	<10	<1	0.18	<10	2.2	609	3	0.03	39	450	7	0.85	2	10	320	<0.01	<10	<10	59	<10	152
LRC 06-12 435-440	<0.005	<0.2	0.38	18	<10	190	0.5	<2	6.35	2.4	14	16	72	4.37	<10	<1	0.19	<10	2.55	658	8	0.03	73	480	8	1.51	3	10	432	<0.01	<10	<10	61	<10	321
LRC 06-12 440-445	<0.005	<0.2	0.41	18	<10	260	0.6	<2	5.62	1.8	17	22	84	4.88	<10	<1	0.19	<10	2.72	575	7	0.03	71	540	10	1.49	2	10	444	<0.01	<10	<10	73	<10	270
LRC 06-12 445-450	<0.005	<0.2	0.42	<2	<10	360	0.8	<2	5.95	<0.5	22	52	88	4.5	<10	1	0.15	20	3.22	790	1	0.02	45	1670	11	0.26	<2	12	479	<0.01	<10	<10	100	<10	84
LRC 06-12 450-455	<0.005	<0.2	0.52	2	<10	380	1.1	<2	6.13	<0.5	27	64	111	5.5	<10	<1	0.18	20	3.31	980	1	0.02	50	2130	12	0.18	<2	17	588	0.01	<10	<10	125	<10	88
LRC 06-12 455-460	<0.005	<0.2	0.42	10	<10	300	0.7	<2	7.02	0.9	22	51	87	4.88	<10	1	0.14	10	3.04	740	3	0.03	65	1140	10	0.89	<2	12	395	<0.01	<10	<10	108	<10	162
LRC 06-12 460-465	<0.005	0.2	0.49	18	<10	220	0.6	<2	3.82	4.6	17	25	95	5.12	<10	<1	0.21	<10	2.14	536	11	0.03	79	670	10	2.05	3	9	199	<0.01	<10	<10	102	<10	551
LRC 06-12 465-470	<0.005	0.3	0.47	15	<10	160	0.5	<2	4.82	2	14	23	75	4.49	<10	<1	0.2	<10	2.4	609	5	0.03	60	520	9	1.7	3	10	255	<0.01	<10	<10	66	<10	284
LRC 06-12 470-475	<0.005	<0.2	0.52	23	<10	190	0.5	<2	4.58	1.8	16	20	76	4.69	<10	<1	0.24	<10	2.19	582	8	0.03	64	580	9	1.95	3	10	304	<0.01	<10	<10	67	<10	275
LRC 06-12 475-480	0.006	<0.2	0.49	18	<10	250	0.5	<2	4.71	2.1	15	20	74	4.45	<10	1	0.24	<10	2.16	611	5	0.03	57	540	10	1.5	<2	11	274	<0.01	<10	<10	73	<10	298
LRC 06-12 480-485	<0.005	<0.2	0.38	22	<10	230	<0.5	<2	6.08	4.1	13	15	72	4.56	<10	<1	0.18	<10	2.31	638	11	0.03	59	460	8	1.6	3	10	421	<0.01	<10	<10	70	<10	510
LRC 06-12 485-490	0.014	<0.2	0.4	16	<10	300	<0.5	<2	5.83	5.8	11	20	64	3.96	<10	<1	0.17	<10	2.61	607	18	0.03	61	290	7	1.24	4	11	397	<0.01	<10	10	104	<10	646
LRC 06-12 490-495	0.006	<0.2	0.42	19	<10	300	0.5	<2	5.6	1.6	13	26	63	4.22	<10	<1	0.17	<10	2.57	626	14	0.03	73	620	7	1.4	4	10	432	<0.01	<10	<10	82	<10	263
LRC 06-12 495-500	0.005	<0.2	0.39	12	<10	350	0.5	<2	6.41	0.9	12	26	55	3.59	<10	<1	0.19	<10	2.46	427	12	0.03	112	340	8	1.18	<2	8	384	<0.01	<10	<10	52	<10	187

VA06094742 - Finalized
CLIENT : "SHK - Alpha Gold Corp."
of SAMPLES : 88
DATE RECEIVED : 2006-09-01 DATE FINALIZED : 2006-10-08
PROJECT : "Lust Dust"
CERTIFICATE COMMENTS : ""
PO NUMBER : ""

SAMPLE DESCRIPTION	Au ppm	Ag ppm	Al %	As ppm	B ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
LRC-06-13 60-65	<0.005	<0.2	0.04	5	<10	10	<0.5	<2	>25.0	<0.5	1	6	21	0.11	<10	<1	0.01	<10	0.27	27	<1	0.01	2	70	<2	<0.01	<2	<1	240	<0.01	<10	10	3	<10	8
LRC-06-13 65-70	<0.005	<0.2	0.03	3	<10	10	<0.5	<2	>25.0	0.5	1	5	2	0.08	<10	1	<0.01	<10	0.71	21	<1	0.01	1	60	<2	<0.01	<2	<1	295	<0.01	<10	10	3	<10	10
LRC-06-13 70-75	<0.005	<0.2	0.02	4	<10	20	<0.5	<2	22.6	<0.5	2	3	6	0.12	<10	2	<0.01	<10	9.86	31	<1	0.01	6	40	<2	<0.01	4	<1	146	<0.01	<10	10	1	<10	22
LRC-06-13 75-80	<0.005	<0.2	0.02	3	<10	20	<0.5	<2	>25.0	0.7	1	8	9	0.06	<10	1	<0.01	<10	0.22	25	<1	0.01	2	30	<2	<0.01	2	<1	300	<0.01	<10	10	2	<10	9
LRC-06-13 80-85	<0.005	0.2	0.03	<2	<10	10	<0.5	<2	>25.0	0.6	1	7	12	0.06	<10	1	<0.01	<10	0.23	21	<1	0.01	1	40	6	<0.01	2	<1	283	<0.01	<10	10	2	<10	11
LRC-06-13 85-90	<0.005	<0.2	0.02	5	<10	10	<0.5	2	>25.0	0.6	1	6	3	0.04	<10	1	<0.01	<10	0.19	16	<1	0.01	2	40	2	<0.01	2	<1	301	<0.01	<10	10	2	<10	12
LRC-06-13 90-95	<0.005	0.3	0.07	<2	<10	10	<0.5	<2	>25.0	0.5	1	5	3	0.1	<10	1	<0.01	<10	0.28	28	<1	0.01	5	60	<2	<0.01	2	<1	226	0.01	<10	10	4	<10	8
LRC-06-13 95-100	0.005	<0.2	0.02	3	<10	10	<0.5	<2	>25.0	0.5	1	4	3	0.04	<10	1	<0.01	<10	0.19	17	<1	0.01	<1	50	<2	<0.01	2	<1	254	<0.01	<10	10	2	<10	9
LRC-06-13 100-105	<0.005	<0.2	0.01	<2	<10	10	<0.5	<2	>25.0	0.6	<1	4	2	0.03	<10	1	<0.01	<10	0.19	17	<1	0.01	3	150	<2	<0.01	<2	<1	268	<0.01	<10	10	2	<10	8
LRC-06-13 105-110	<0.005	<0.2	0.01	<2	<10	10	<0.5	<2	>25.0	0.6	1	4	2	0.02	<10	1	<0.01	<10	0.24	16	<1	0.01	3	70	<2	<0.01	<2	<1	228	<0.01	<10	10	1	<10	7
LRC-06-13 110-115	<0.005	<0.2	0.01	<2	<10	10	<0.5	<2	>25.0	0.5	1	4	2	0.02	<10	1	<0.01	<10	0.22	17	<1	0.01	<1	50	<2	<0.01	<2	<1	254	<0.01	<10	10	2	<10	7
LRC-06-13 115-120	<0.005	<0.2	0.03	3	<10	10	<0.5	<2	>25.0	0.5	<1	5	4	0.06	<10	1	<0.01	<10	0.23	23	<1	0.01	3	50	2	<0.01	2	<1	302	<0.01	<10	10	2	<10	9
LRC-06-13 120-125	<0.005	<0.2	0.01	4	<10	10	<0.5	<2	>25.0	<0.5	1	3	4	0.03	<10	1	<0.01	<10	1.09	14	<1	0.01	3	40	<2	<0.01	4	<1	399	<0.01	<10	10	2	<10	11
LRC-06-13 125-130	<0.005	<0.2	0.01	2	<10	10	<0.5	<2	>25.0	<0.5	1	2	3	0.04	<10	1	<0.01	<10	2.34	14	<1	0.01	2	30	<2	<0.01	2	<1	1270	<0.01	<10	10	2	<10	14
LRC-06-13 130-135	<0.005	0.2	0.01	<2	<10	10	<0.5	<2	>25.0	<0.5	1	2	3	0.02	<10	1	<0.01	<10	0.47	13	<1	0.01	1	20	<2	<0.01	<2	<1	1590	<0.01	<10	10	1	<10	6
LRC-06-13 135-140	<0.005	0.2	0.02	<2	<10	10	<0.5	<2	>25.0	<0.5	1	3	6	0.06	<10	1	<0.01	<10	0.82	21	<1	0.01	1	30	<2	<0.01	4	<1	1550	<0.01	<10	10	2	<10	8
LRC-06-13 140-145	<0.005	<0.2	0.01	<2	<10	10	<0.5	<2	>25.0	0.7	1	5	5	0.03	<10	1	<0.01	<10	0.21	21	<1	0.01	1	30	<2	<0.01	3	<1	541	<0.01	<10	10	2	<10	8
LRC-06-13 145-150	<0.005	<0.2	0.01	<2	<10	10	<0.5	<2	>25.0	0.5	1	5	3	0.05	<10	<1	<0.01	<10	0.27	21	<1	0.01	2	60	<2	<0.01	2	<1	362	<0.01	<10	10	2	<10	12
LRC-06-13 150-155	<0.005	<0.2	0.01	2	<10	10	<0.5	<2	>25.0	0.6	1	5	3	0.05	<10	<1	<0.01	<10	0.31	20	<1	0.01	3	110	<2	<0.01	3	<1	371	<0.01	<10	10	2	<10	11
LRC-06-13 155-160	<0.005	<0.2	0.02	3	<10	10	<0.5	<2	>25.0	<0.5	<1	5	2	0.04	<10	<1	<0.01	<10	0.17	17	<1	0.01	<1	430	<2	<0.01	<2	<1	397	<0.01	<10	10	2	<10	11
LRC-06-13 160-165	<0.005	<0.2	0.01	4	<10	20	<0.5	<2	>25.0	<0.5	1	4	2	0.04	<10	1	<0.01	<10	2.64	15	<1	0.01	3	140	<2	<0.01	5	<1	453	<0.01	<10	10	2	<10	14
LRC-06-13 165-170	<0.005	<0.2	0.01	3	<10	20	<0.5	<2	>25.0	<0.5	1	3	2	0.03	<10	1	<0.01	<10	0.56	15	<1	0.01	1	50	2	<0.01	3	<1	642	<0.01	<10	10	2	<10	5
LRC-06-13 170-175	<0.005	<0.2	0.01	<2	<10	20	<0.5	<2	>25.0	<0.5	2	3	2	0.04	<10	1	<0.01	<10	1.8	20	<1	0.01	1	80	<2	<0.01	5	<1	742	<0.01	<10	10	2	<10	9
LRC-06-13 175-180	<0.005	<0.2	0.03	2	<10	20	<0.5	<2	>25.0	<0.5	2	5	5	0.14	<10	1	<0.01	<10	2.69	42	<1	0.02	5	170	3	<0.01	12	<1	331	<0.01	<10	10	3	<10	11
LRC-06-13 180-185	<0.005	<0.2	0.01	<2	<10	20	<0.5	<2	>25.0	<0.5	1	6	2	0.07	<10	<1	<0.01	<10	0.53	26	<1	0.01	4	110	<2	<0.01	11	<1	306	<0.01	<10	10	2	<10	10
LRC-06-13 185-190	<0.005	<0.2	0.02	<2	<10	10	<0.5	<2	>25.0	<0.5	1	7	3	0.05	<10	1	<0.01	<10	0.28	23	<1	0.01	1	50	<2	<0.01	4	<1	290	<0.01	<10	10	2	<10	12
LRC-06-13 190-195	<0.005	<0.2	0.01	2	<10	10	<0.5	<2	>25.0	0.5	1	8	2	0.06	<10	4	<0.01	<10	0.21	54	<1	0.01	4	90	<2	<0.01	6	<1	296	<0.01	<10	10	2	<10	11
LRC-06-13 195-200	<0.005	<0.2	0.01	2	<10	10	<0.5	<2	>25.0	<0.5	1	4	3	0.06	<10	1	<0.01	<10	1.82	25	<1	0.01	3	40	<2	<0.01	8	<1	241	<0.01	<10	10	2	<10	12
LRC-06-13 200-205	<0.005	<0.2	0.02	3	<10	10	<0.5	<2	>25.0	0.6	1	6	3	0.07	<10	1	<0.01	<10	0.26	38	<1	0.01	5	70	<2	<0.01	5	<1	278	<0.01	<10	10	2	<10	7
LRC-06-13 205-210	<0.005	<0.2	0.02	2	<10	10	<0.5	<2	>25.0	0.6	2	8	5	0.11	<10	8	<0.01	<10	0.83	73	<1	0.01	6	120	<2	<0.01	8	<1	278	<0.01	<10	10	3	<10	19
LRC-06-13 210-215	0.005	<0.2	0.02	4	<10	10	<0.5	<2	>25.0	0.5	1	7	6	0.11	<10	6	<0.01	<10	0.5	89	<1	0.01	6	70	<2	<0.01	3	<1	260	<0.01	<10	10	3	<10	22
LRC-06-13 215-220	<0.005	<0.2	0.03	<2	<10	20	<0.5	<2	>25.0	0.6	2	7	4	0.19	<10	3	<0.01	<10	0.24	94	<1	0.01	4	50	3	<0.01	6	<1	230	<0.01	<10	10	4	<10	13
LRC-06-13 220-225	<0.005	<0.2	0.01	<2	<10	10	<0.5	<2	>25.0	0.5	2	6	3	0.1	<10	1	<0.01	<10	0.2	67	<1	0.01	4	40	2	<0.01	5	<1	248	<0.01	<10	10	3	<10	10
LRC-06-13 225-230	<0.005	<0.2	0.02	4	<10	20	<0.5	<2	>25.0	0.7	2	7	3	0.17	<10	3	<0.01	<10	1.28	82	<1	0.01	7	90	<2	<0.01	7	<1	236	<0.01	<10	10	4	<10	19
LRC-06-13 230-235	<0.005	<0.2	0.02	<2	<10	20	<0.5	<2	>25.0	0.7	1	6	4	0.14	<10	2	<0.01	<10	0.88	61	<1	0.01	7	90	<2	<0.01	8	<1	225	<0.01	<10	10	3	<10	16
LRC-06-13 235-240	<0.005	<0.2	0.04	4	<10	10	<0.5	<2	>25.0	<0.5	2	4	6	0.18	<10	2	<0.01	<10	2.82	103	<1	0.01	9	60	<2	<0.01	10	<1	196	<0.01	<10	10	4	<10	24
LRC-06-13 240-245	<0.005	<0.2	0.03	6	<10	10	<0.5	<2	>25.0	0.6	1	6	5	0.14	<10	6	<0.01	<10	0.29	119	<1	0.01	9	60	<2	<0.01	7	1	226	<0.01	<10	10	4	<10	13
LRC-06-13 245-250	<0.005	<0.2	0.03	2	<10	10	<0.5	<2	>25.0	0.5	2	6	5	0.11	<10	3	<0.01	<10	0.87	71	<1	0.01	10	70	<2	<0.01	8	<1	220	<0.01	<10	10	4	<10	14
LRC-06-13 250-255	<0.005	<0.2	0.02	5	<10	10</																													

VA06094742 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 88
 DATE RECEIVED : 2006-09-01 DATE FINALIZED : 2006-10-08
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE	Au-AA23	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41
DESCRIPTION	Au	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn			
	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm		
LRC-06-13 475-480	<0.005	<0.2	0.65	20	10	240	0.6	<2	4.21	4.3	18	24	95	4.71	<10	<1	0.24	<10	2.08	539	12	0.03	78	570	10	2.01	4	11	235	<0.01	<10	<10	95	<10	494			
LRC-06-13 480-485	<0.005	0.2	0.63	19	10	230	0.7	<2	3.43	2.9	19	22	95	4.74	<10	1	0.26	<10	1.94	521	9	0.03	69	650	10	2.02	4	11	186	<0.01	<10	<10	84	<10	355			
LRC-06-13 485-490	<0.005	0.2	0.59	15	10	210	0.6	<2	4.17	2.5	17	24	79	4.55	<10	<1	0.22	<10	2.02	586	8	0.03	64	460	11	1.54	3	11	211	<0.01	<10	<10	76	<10	340			
LRC-06-13 490-495	<0.005	<0.2	0.56	15	10	190	0.6	<2	5.2	1.5	15	26	66	4.26	<10	<1	0.2	<10	2.05	671	5	0.03	51	480	10	1.39	2	11	236	<0.01	<10	<10	75	<10	229			
LRC-06-13 495-500	<0.005	<0.2	0.45	3	10	130	<0.5	<2	4.33	<0.5	5	11	13	1.79	<10	<1	0.13	<10	1.18	360	1	0.03	28	210	5	0.13	<2	3	197	<0.01	<10	<10	14	<10	49			

VA06094743 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 94
 DATE RECEIVED : 2006-09-01 DATE FINALIZED : 2006-10-06
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE DESCRIPTION	Au	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn
	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	
LRC-06-14 445-450	<0.005	<0.2	0.32	34	20	350	<0.5	<2	1.01	<0.5	4	20	32	1.59	<10	1	0.13	<10	0.32	95	2	0.01	19	120	6	1.18	2	28	<0.01	<10	<10	6	<10	50	
LRC-06-14 450-455	<0.005	<0.2	0.3	32	10	300	<0.5	<2	0.95	<0.5	4	6	25	1.41	<10	1	0.12	<10	0.46	98	<1	0.01	16	90	6	0.35	2	31	<0.01	<10	<10	6	<10	43	
LRC-06-14 455-460	<0.005	<0.2	0.22	13	10	240	<0.5	<2	0.43	<0.5	4	25	20	1.08	<10	<1	0.09	<10	0.28	81	<1	<0.01	11	80	6	0.16	<2	1	18	<0.01	<10	<10	5	<10	35
LRC-06-14 460-465	<0.005	<0.2	0.34	28	<10	400	<0.5	<2	0.62	<0.5	4	10	24	1.33	<10	<1	0.11	10	0.36	115	<1	0.01	17	160	6	0.22	<2	2	22	<0.01	<10	<10	8	<10	42
LRC-06-14 465-470	<0.005	<0.2	0.33	18	10	480	<0.5	<2	0.95	<0.5	4	22	23	1.53	<10	<1	0.11	<10	0.55	166	<1	0.01	16	140	6	0.2	<2	2	30	<0.01	<10	<10	8	<10	42
LRC-06-14 470-475	<0.005	<0.2	0.36	8	<10	400	<0.5	<2	0.66	<0.5	4	5	21	1.27	<10	<1	0.1	10	0.43	112	<1	0.01	12	150	4	0.18	<2	2	22	<0.01	<10	<10	6	<10	37
LRC-06-14 475-480	<0.005	<0.2	0.53	<2	<10	460	<0.5	<2	1.56	<0.5	3	24	20	1.35	<10	<1	0.09	<10	0.49	176	<1	0.01	14	210	7	0.45	<2	2	47	<0.01	<10	<10	7	<10	38
LRC-06-14 480-485	<0.005	<0.2	0.45	28	<10	700	<0.5	<2	7.15	<0.5	2	7	18	1.21	<10	<1	0.09	<10	0.48	219	<1	0.01	12	260	6	0.58	2	2	135	<0.01	<10	<10	6	<10	36
LRC-06-14 485-490	<0.005	0.2	0.14	5	<10	1560	<0.5	<2	21.7	0.7	2	9	21	0.34	<10	<1	0.02	10	0.53	1270	<1	0.02	10	490	4	<0.01	<2	2	315	<0.01	<10	10	2	<10	32
LRC-06-14 490-495	<0.005	0.2	0.06	24	<10	1480	<0.5	<2	>25.0	1	<1	2	15	0.3	<10	<1	0.01	10	0.42	1470	<1	0.02	2	740	6	<0.01	<2	1	343	<0.01	<10	10	1	<10	31
LRC-06-14 495-500	<0.005	<0.2	0.46	10	<10	380	<0.5	<2	4.05	<0.5	2	5	17	0.77	<10	<1	0.03	10	0.67	370	<1	0.01	11	1090	6	0.48	<2	2	123	<0.01	10	<10	4	<10	39

VA06101104 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 98
 DATE RECEIVED : 2006-09-13 DATE FINALIZED : 2006-10-16
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE DESCRIPTION	Au	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn
	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
LRC 06-22 425-430	<0.005	<0.2	5.13	9	10	100	<0.5	<2	5.08	<0.5	31	215	147	5.77	10	<1	0.1	<10	2.95	818	2	0.06	117	540	<2	0.09	<2	20	78	0.38	<10	<10	157	<10	63
LRC 06-22 430-435	<0.005	<0.2	6.17	10	10	100	<0.5	<2	7.04	<0.5	37	250	115	6.56	10	<1	0.06	<10	3.3	941	<1	0.06	138	320	<2	0.03	<2	28	131	0.38	<10	<10	168	<10	64
LRC 06-22 435-440	<0.005	<0.2	5.79	10	10	100	<0.5	<2	8.18	<0.5	32	255	106	5.83	10	1	0.07	<10	3.15	936	<1	0.06	137	320	<2	0.03	<2	26	161	0.34	<10	<10	142	<10	59
LRC 06-22 440-445	<0.005	<0.2	5.63	14	10	90	<0.5	<2	7.36	<0.5	34	212	147	6.44	10	<1	0.06	<10	3.17	924	<1	0.06	123	370	<2	0.04	<2	28	143	0.39	<10	<10	173	<10	69
LRC 06-22 445-450	<0.005	<0.2	5.86	9	10	100	<0.5	<2	6.04	<0.5	38	172	173	7.31	10	<1	0.08	<10	3.14	920	<1	0.06	106	450	2	0.06	3	30	106	0.45	<10	<10	212	<10	78
LRC 06-22 450-455	<0.005	<0.2	5.41	6	10	90	<0.5	<2	5.16	<0.5	37	101	190	7.76	10	<1	0.07	<10	2.74	851	<1	0.06	73	500	<2	0.05	2	32	84	0.49	<10	<10	233	<10	83
LRC 06-22 455-460	0.011	<0.2	5.83	<2	10	90	<0.5	<2	5.27	<0.5	37	126	202	8.33	10	<1	0.07	<10	2.97	930	<1	0.07	89	460	<2	0.04	2	34	75	0.5	<10	<10	242	<10	91
LRC 06-22 460-465	<0.005	<0.2	4.97	8	10	80	<0.5	<2	6.54	<0.5	31	73	184	7.05	10	2	0.08	<10	2.64	905	<1	0.05	65	520	<2	0.07	2	26	100	0.43	<10	<10	222	<10	84
LRC 06-22 465-470	<0.005	<0.2	5.06	5	10	100	<0.5	<2	6.35	<0.5	32	117	171	6.5	10	<1	0.08	<10	2.82	865	1	0.05	74	480	3	0.1	2	25	119	0.41	<10	<10	204	<10	78
LRC 06-22 470-475	<0.005	<0.2	3.08	6	10	50	<0.5	<2	13.9	<0.5	17	46	130	3.67	10	<1	0.12	<10	2.22	882	<1	0.03	44	620	<2	0.19	<2	12	314	0.26	<10	<10	125	<10	67
LRC 06-22 475-480	<0.005	<0.2	4.38	12	10	70	<0.5	<2	9.8	<0.5	29	68	150	6.06	10	2	0.08	<10	2.47	962	<1	0.05	55	530	<2	0.1	<2	24	203	0.39	<10	<10	207	<10	81
LRC 06-22 480-485	<0.005	<0.2	4.84	7	10	70	<0.5	<2	8.56	<0.5	32	131	173	5.53	10	2	0.07	<10	3.05	1030	<1	0.05	92	370	<2	0.07	<2	20	135	0.32	<10	<10	165	<10	62
LRC 06-22 485-490	<0.005	<0.2	6.06	8	10	90	<0.5	<2	5.41	<0.5	39	323	202	6.06	10	<1	0.08	<10	3.89	919	<1	0.05	164	300	<2	0.03	<2	24	81	0.36	<10	<10	155	<10	59
LRC 06-22 490-495	<0.005	<0.2	6.07	9	10	110	<0.5	<2	5.25	<0.5	37	331	105	6.4	10	<1	0.09	<10	3.92	862	<1	0.05	162	320	<2	0.03	<2	24	108	0.38	<10	<10	156	<10	60
LRC 06-22 495-500	<0.005	<0.2	6.64	13	10	120	<0.5	<2	5.94	<0.5	40	338	214	6.55	10	1	0.09	<10	4.06	973	<1	0.05	185	310	<2	0.03	<2	26	99	0.38	<10	<10	170	<10	65

VA06101105 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 97
 DATE RECEIVED : 2006-09-13 DATE FINALIZED : 2006-10-19
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE DESCRIPTION	Au	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn
	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
LRC 06-15 430-435	<0.005	<0.2	2.59	12	10	50	<0.5	<2	7.52	<0.5	17	34	173	4	10	1	0.07	<10	1.85	1230	2	0.01	28	600	2	1.01	<2	9	138	0.08	<10	<10	223	<10	62
LRC 06-15 435-440	0.006	<0.2	2.78	9	<10	70	<0.5	<2	8.82	<0.5	18	39	113	3.62	10	1	0.04	<10	2.06	1040	<1	0.01	47	510	3	0.43	<2	12	180	0.14	<10	<10	109	<10	69
LRC 06-15 440-445	<0.005	<0.2	4.68	6	10	60	<0.5	<2	4.22	<0.5	33	241	532	6.09	10	1	0.03	<10	3.43	964	<1	0.01	138	410	3	0.21	<2	20	65	0.39	<10	<10	214	<10	77
LRC 06-15 445-450	<0.005	<0.2	4.5	4	10	80	<0.5	2	3.78	<0.5	32	85	315	6.95	10	<1	0.03	<10	2.9	874	<1	0.03	70	540	3	0.26	2	23	63	0.3	<10	<10	231	<10	90
LRC 06-15 450-455	<0.005	<0.2	4.62	14	10	60	<0.5	3	3.31	<0.5	35	259	109	5.26	10	2	0.04	<10	3.57	683	<1	0.02	176	250	<2	0.03	4	18	46	0.22	<10	<10	133	<10	55
LRC 06-15 455-460	<0.005	<0.2	4.22	9	10	50	<0.5	<2	3.73	<0.5	35	258	117	4.74	10	1	0.04	<10	3.74	771	<1	0.02	197	220	7	0.04	<2	15	37	0.19	10	<10	98	<10	58
LRC 06-15 460-465	<0.005	<0.2	3.53	10	<10	40	<0.5	3	4.81	<0.5	33	85	156	6.23	10	3	0.07	<10	2.7	935	<1	0.02	101	390	<2	0.15	<2	23	55	0.03	<10	<10	101	<10	62
LRC 06-15 465-470	0.006	0.2	1.35	84	<10	260	<0.5	2	14.8	<0.5	24	34	113	4.67	<10	109	0.04	<10	1.02	597	1	0.02	57	310	5	0.75	21	18	109	0.01	<10	<10	69	<10	97
LRC 06-15 470-475	<0.005	0.3	0.6	10	<10	40	<0.5	<2	>25.0	0.5	6	18	42	1.66	<10	73	0.02	<10	0.5	266	<1	0.02	19	210	<2	<0.01	6	7	140	0.01	<10	<10	25	<10	60
LRC 06-15 475-480	0.007	<0.2	2.68	12	<10	70	<0.5	<2	16.3	<0.5	18	93	143	3.2	10	121	0.05	<10	1.87	501	<1	0.02	74	290	2	<0.01	5	11	107	0.14	<10	<10	89	<10	63
LRC 06-15 480-485	0.005	<0.2	0.39	6	<10	30	<0.5	2	>25.0	0.9	3	18	22	1.9	<10	147	0.01	<10	0.37	319	<1	0.02	16	180	<2	<0.01	7	4	168	0.02	<10	<10	18	<10	66
LRC 06-15 485-490	<0.005	<0.2	0.12	7	<10	20	<0.5	<2	>25.0	0.8	1	8	9	1.48	<10	40	0.01	<10	0.17	212	<1	0.01	8	130	<2	<0.01	8	3	178	<0.01	<10	<10	9	<10	56
LRC 06-15 490-495	0.006	<0.2	0.19	11	<10	20	<0.5	<2	>25.0	0.6	2	11	11	1.22	<10	65	0.01	<10	0.21	185	<1	0.02	7	170	2	<0.01	9	3	188	0.01	<10	<10	12	<10	43
LRC 06-15 495-500	0.008	<0.2	0.25	120	<10	50	<0.5	<2	>25.0	1.4	3	11	19	0.93	<10	95	0.03	<10	0.19	128	1	0.01	12	200	2	0.6	32	2	184	0.01	<10	<10	12	<10	42

VA06101106 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 93
 DATE RECEIVED : 2006-09-13 DATE FINALIZED : 2006-10-18
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE DESCRIPTION	Au	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn
	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	
LRC 06-16 450-455	0.007	<0.2	0.55	56	<10	80	<0.5	<2	16.7	<0.5	7	40	19	1.43	<10	34	0.05	<10	0.98	343	<1	0.02	71	300	3	<0.01	17	3	84	0.03	<10	<10	20	<10	69
LRC 06-16 455-460	0.008	<0.2	0.56	56	<10	80	<0.5	<2	16.7	<0.5	6	30	19	1.52	<10	59	0.06	10	0.97	362	<1	0.02	61	330	4	0.05	17	3	79	0.03	<10	<10	21	<10	71
LRC 06-16 460-465	<0.005	0.2	0.4	48	<10	60	<0.5	<2	23.7	0.7	3	27	12	0.97	<10	35	0.04	<10	0.72	220	<1	0.01	43	220	4	<0.01	8	2	129	0.03	<10	<10	15	<10	53
LRC 06-16 465-470	0.005	0.2	0.62	45	<10	90	<0.5	<2	15.7	0.6	8	51	17	1.82	<10	66	0.06	<10	2.07	395	2	0.02	90	260	4	0.05	16	3	90	0.03	<10	<10	20	<10	57
LRC 06-16 470-475	<0.005	0.2	0.68	15	<10	60	<0.5	<2	17.2	<0.5	16	123	11	2.12	<10	11	0.05	<10	6.65	607	<1	0.01	210	140	2	0.08	3	7	135	0.01	<10	<10	24	<10	33
LRC 06-16 475-480	0.138	<0.2	0.31	20	<10	50	<0.5	<2	24.1	<0.5	9	108	8	1.26	<10	10	0.03	<10	4.74	299	<1	0.01	155	120	4	<0.01	<2	4	149	<0.01	10	<10	14	<10	27
LRC 06-16 480-485	0.009	0.3	0.29	32	<10	40	<0.5	<2	>25.0	0.7	3	28	6	0.67	<10	15	0.03	<10	0.81	162	<1	0.01	50	190	4	<0.01	4	1	142	0.01	<10	<10	10	<10	44
LRC 06-16 485-490	0.006	<0.2	0.47	44	<10	70	<0.5	<2	21.9	0.6	4	35	14	1.25	<10	44	0.05	<10	0.73	295	1	0.02	53	260	4	<0.01	14	2	103	0.03	<10	<10	16	<10	56
LRC 06-16 490-495	<0.005	0.2	0.22	15	<10	30	<0.5	<2	>25.0	0.8	5	35	3	0.58	<10	12	0.02	<10	0.97	192	<1	0.01	52	110	<2	<0.01	2	2	132	0.01	<10	<10	8	<10	27
LRC 06-16 495-500	<0.005	<0.2	0.24	8	<10	20	<0.5	<2	>25.0	<0.5	3	34	3	0.41	<10	4	0.01	<10	0.92	124	<1	0.01	49	100	2	<0.01	<2	2	165	<0.01	<10	<10	7	<10	11

VA06101107 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 77
 DATE RECEIVED : 2006-09-13 DATE FINALIZED : 2006-10-18
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE DESCRIPTION	Au	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn	
	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
LRC 06-18 50-55	0.009	<0.2	1.01	6	10	360	<0.5	<2	0.94	<0.5	8	10	62	2.02	<10	1	0.27	10	0.6	884	7	0.02	27	260	6	0.5	3	2	62	0.01	<10	<10	17	<10	68	
LRC 06-18 55-60	<0.005	0.2	1	6	10	340	<0.5	<2	0.68	<0.5	7	10	60	1.99	<10	<1	0.27	10	0.59	662	7	0.02	26	270	7	0.56	<2	2	48	0.01	<10	<10	18	<10	71	
LRC 06-18 60-65	0.005	0.2	1.01	8	10	330	<0.5	<2	1.56	<0.5	8	12	62	1.94	<10	<1	0.25	10	0.61	1105	6	0.02	34	260	4	0.46	<2	3	101	<0.01	<10	<10	15	<10	63	
LRC 06-18 65-70	<0.005	<0.2	1.49	7	10	310	<0.5	<2	2.92	<0.5	11	36	62	2.76	<10	1	0.25	10	1.11	1045	4	0.02	45	570	4	0.65	<2	4	201	0.01	<10	<10	30	<10	69	
LRC 06-18 70-75	<0.005	<0.2	1.77	8	<10	210	<0.5	<2	4.83	<0.5	11	54	43	2.76	<10	1	0.18	<10	1.5	1105	1	0.02	47	530	5	0.28	<2	4	369	0.01	<10	<10	50	<10	49	
LRC 06-18 75-80	0.023	<0.2	1.72	6	10	210	<0.5	<2	1.97	<0.5	9	49	67	3.45	10	<1	0.17	10	1.19	911	1	0.01	47	590	6	0.27	<2	4	129	0.01	<10	<10	51	<10	62	
LRC 06-18 80-85	<0.005	<0.2	1.12	3	<10	250	<0.5	5	1.17	<0.5	5	24	121	2.53	<10	1	0.18	10	0.65	668	1	0.01	31	790	14	0.22	<2	2	72	0.01	<10	<10	27	<10	51	
LRC 06-18 85-90	<0.005	<0.2	2.48	8	<10	270	<0.5	<2	3.17	<0.5	18	114	72	4.05	10	<1	0.2	10	2.13	956	2	0.02	68	760	4	0.39	2	9	209	0.1	<10	<10	82	<10	85	
LRC 06-18 90-95	<0.005	<0.2	1.68	6	10	290	<0.5	3	2.07	<0.5	14	53	70	2.89	<10	<1	0.28	<10	1.37	753	3	0.01	51	550	7	0.54	<2	5	125	0.05	<10	<10	46	<10	84	
LRC 06-18 95-100	0.005	<0.2	1.8	<2	10	290	<0.5	<2	2.71	<0.5	13	43	69	3.11	10	<1	0.27	<10	1.52	991	3	0.02	51	630	5	0.63	<2	4	158	0.07	<10	<10	44	<10	85	
LRC 06-18 100-105	<0.005	0.2	1.7	7	10	340	<0.5	2	2.12	<0.5	12	32	68	3.04	<10	1	0.25	<10	1.33	955	4	0.02	48	570	7	0.68	2	4	122	0.02	<10	<10	32	<10	83	
LRC 06-18 105-110	<0.005	<0.2	1.35	8	<10	270	<0.5	<2	2.63	<0.5	9	26	64	2.49	<10	1	0.22	<10	1.07	1030	3	0.02	37	460	7	0.61	<2	3	151	0.01	<10	<10	27	<10	67	
LRC 06-18 110-115	<0.005	0.2	1.83	<2	10	400	<0.5	2	2.04	<0.5	13	35	75	3.17	<10	<1	0.31	10	1.38	949	5	0.02	51	610	10	0.7	<2	4	118	0.01	<10	<10	35	<10	92	
LRC 06-18 115-120	<0.005	0.3	1.23	11	10	240	<0.5	<2	2.75	<0.5	9	23	60	2.34	<10	1	0.17	<10	1.02	1020	2	0.01	36	400	7	0.56	<2	3	150	0.01	<10	<10	24	<10	56	
LRC 06-18 120-125	<0.005	<0.2	1.29	13	<10	230	<0.5	3	4.43	<0.5	7	24	50	2.47	<10	1	0.17	<10	1.08	957	2	0.02	31	440	10	0.81	<2	3	249	0.01	<10	<10	26	<10	48	
LRC 06-18 125-130	<0.005	<0.2	3.25	21	<10	370	<0.5	2	2.25	<0.5	26	141	77	5.03	10	<1	0.17	10	2.87	1090	2	0.02	98	880	5	0.39	2	8	149	0.02	<10	<10	89	<10	98	
LRC 06-18 130-135	<0.005	0.2	3.62	33	10	330	<0.5	3	1.9	<0.5	29	185	76	5.62	10	<1	0.18	10	3.29	1160	3	0.02	119	870	<2	0.41	<2	11	118	0.07	<10	<10	116	<10	95	
LRC 06-18 135-140	<0.005	<0.2	3.21	20	10	320	<0.5	2	2.22	<0.5	27	140	74	5.26	10	<1	0.2	10	2.78	1095	5	0.03	101	1000	6	0.56	<2	10	122	0.13	<10	<10	100	<10	110	
LRC 06-18 140-145	0.005	0.2	1.88	5	10	370	<0.5	2	1.81	<0.5	15	49	71	3.31	10	1	0.26	10	1.48	770	5	0.02	55	590	7	0.64	<2	5	94	0.05	<10	<10	45	<10	93	
LRC 06-18 145-150	<0.005	0.3	1.53	6	10	280	<0.5	2	2.02	<0.5	12	34	70	2.9	<10	1	0.23	10	1.21	791	3	0.02	46	480	8	0.71	2	3	91	0.02	<10	<10	31	<10	75	
LRC 06-18 150-155	<0.005	<0.2	1.54	9	10	310	<0.5	<2	2.86	<0.5	10	33	64	2.68	<10	<1	0.22	10	1.26	843	3	0.02	40	460	8	0.6	<2	3	140	0.02	<10	<10	30	<10	66	
LRC 06-18 155-160	<0.005	<0.2	1.47	5	10	330	<0.5	<2	2.54	<0.5	11	26	69	2.57	<10	<1	0.23	10	1.22	746	3	0.01	38	460	5	0.68	<2	3	113	0.01	<10	<10	26	<10	73	
LRC 06-18 160-165	<0.005	0.2	1.42	8	10	330	<0.5	2	3.72	<0.5	9	24	66	2.42	<10	<1	0.24	10	1.15	635	4	0.02	33	380	7	0.65	<2	3	136	0.01	<10	<10	26	<10	65	
LRC 06-18 165-170	<0.005	<0.2	1.28	11	10	350	<0.5	2	3.11	<0.5	9	20	79	2.39	<10	<1	0.22	10	0.99	631	3	0.01	31	380	7	0.75	<2	3	103	<0.01	<10	<10	23	<10	64	
LRC 06-18 170-175	<0.005	0.3	2.42	9	10	330	<0.5	3	2.89	<0.5	16	63	72	3.8	10	1	0.19	10	2.06	731	3	0.02	53	380	2	0.67	<2	8	93	0.11	<10	<10	66	<10	68	
LRC 06-18 175-180	0.006	0.2	2.53	6	10	320	<0.5	<2	3.11	<0.5	17	66	70	4.04	10	1	0.18	10	2.16	760	3	0.02	54	380	6	0.68	<2	8	91	0.11	<10	<10	68	<10	70	
LRC 06-18 180-185	<0.005	<0.2	3.95	<2	10	280	<0.5	<2	2.73	<0.5	26	131	65	5.39	10	<1	0.16	10	3.53	822	2	0.03	86	460	3	0.46	2	10	82	0.22	<10	<10	107	<10	76	
LRC 06-18 185-190	<0.005	<0.2	4.52	3	10	210	<0.5	<2	2.58	<0.5	31	136	52	5.83	10	1	0.1	<10	4.27	792	1	0.03	94	470	<2	0.24	2	11	74	0.29	<10	<10	125	<10	68	
LRC 06-18 190-195	<0.005	<0.2	4.77	4	10	280	<0.5	<2	3.78	<0.5	32	163	67	6.07	10	<1	0.08	<10	4.69	887	1	0.04	93	460	<2	0.22	<2	16	106	0.35	<10	<10	163	<10	71	
LRC 06-18 195-200	<0.005	<0.2	4.68	2	10	560	<0.5	<2	6.34	<0.5	30	176	83	5.76	10	1	0.05	<10	4.54	921	1	0.04	84	580	3	0.22	2	19	178	0.31	<10	<10	173	<10	72	
LRC 06-18 200-205	<0.005	<0.2	3.32	<2	10	580	<0.5	<2	5.04	<0.5	21	112	67	4.56	10	<1	0.11	<10	3.12	725	2	0.03	66	410	3	0.65	<2	11	121	0.19	<10	<10	108	<10	61	
LRC 06-18 205-210	<0.005	<0.2	2.53	2	<10	570	<0.5	<2	5.13	<0.5	17	76	69	3.74	10	2	0.16	10	2.35	624	5	0.03	54	490	5	0.7	<2	7	119	0.1	<10	<10	73	<10	79	
LRC 06-18 210-215	<0.005	<0.2	1.81	5	10	220	<0.5	<2	3.37	<0.5	12	53	59	3.05	<10	<1	0.18	10	1.59	437	6	0.03	41	410	6	0.84	<2	6	76	0.1	<10	<10	53	<10	80	
LRC 06-18 215-220	<0.005	<0.2	3.04	4	<10	580	<0.5	<2	4.07	<0.5	22	125	87	4.39	10	1	0.11	<10	3.06	771	2	0.03	62	350	3	0.42	3	13	99	0.18	<10	<10	107	<10	70	
LRC 06-18 220-225	<0.005	<0.2	3.44	3	<10	450	<0.5	<2	5.39	<0.5	24	141	65	5.02	10	1	0.12	20	3.25	837	4	0.04	98	1450	4	0.47	<2	13	121	0.51	<10	<10	120	<10	85	
LRC 06-18 225-230	<0.005	<0.2	4.44	2	<10	510	<0.5	<2	4.3	<0.5	32	207	81	6.13	10	1	0.09	20	4.35	975	4	0.03	114	1140	2	0.3	2	19	101	0.33	<10	<10	168	<10	89	
LRC 06-18 230-235	<0.005	<0.2	2.11	<2	<10	360	<0.5	<2	13.4	<0.5	13	69	39	2.57	<10	<1	0.06	10	3.91	575	1	0.03	43	440	<2	0.21	<2	8	309	0.11	<10	<10	67	<10	49	
LRC 06-18 235-240	<0.005	<0.2	0.42	<2	<10	360	<0.5	<2	20.3	0.5	3	12	13	0.69	<10	1	0.07	<10	1.19	309	<1	0.02	17	350	2	<0.01	2	2	207	0.02	<10	<10	11	<10	40	

VA06101108 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 91
 DATE RECEIVED : 2006-09-13 DATE FINALIZED : 2006-10-17
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE DESCRIPTION	Au-AA23		ME-ICP41		ME-ICP41		ME-ICP41		ME-ICP41		ME-ICP41		ME-ICP41		ME-ICP41		ME-ICP41		ME-ICP41		ME-ICP41		ME-ICP41		ME-ICP41		ME-ICP41		ME-ICP41		ME-ICP41		ME-ICP41		ME-ICP41		ME-ICP41		ME-ICP41	
	Au	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn					
LRC 06-17 45-50	<0.005	<0.2	0.08	20	<10	30	<0.5	<2	>25.0	1	<1	4	3	0.17	<10	1	0.01	<10	0.13	50	1	0.01	8	270	<2	<0.01	2	1	167	<0.01	<10	<10	<10	3	<10	26				
LRC 06-17 50-55	0.006	<0.2	0.07	7	<10	20	<0.5	<2	>25.0	1.3	1	3	2	0.16	<10	1	0.02	<10	0.13	30	1	0.01	6	130	<2	<0.01	<2	1	193	<0.01	<10	<10	3	<10	30					
LRC 06-17 55-60	<0.005	<0.2	0.07	20	<10	40	<0.5	<2	>25.0	1.1	<1	6	2	0.23	<10	1	0.01	<10	0.17	34	<1	0.01	11	110	<2	<0.01	4	1	233	<0.01	<10	<10	2	<10	25					
LRC 06-17 60-65	<0.005	<0.2	0.42	26	<10	340	<0.5	<2	>25.0	0.9	8	67	14	1.04	<10	3	0.04	<10	1.28	227	1	0.01	104	200	3	<0.01	6	4	253	<0.01	<10	<10	20	<10	44					
LRC 06-17 65-70	<0.005	<0.2	0.8	11	10	180	0.5	<2	10.7	<0.5	21	26	90	5.24	<10	2	0.11	10	3.81	1080	2	0.02	41	1560	5	0.32	3	15	318	<0.01	<10	<10	145	<10	100					
LRC 06-17 70-75	<0.005	<0.2	0.79	17	10	280	0.6	<2	7.05	2.1	20	21	97	5.14	<10	<1	0.15	10	2.96	855	9	0.02	50	1160	6	1.17	4	14	312	<0.01	<10	<10	156	<10	322					
LRC 06-17 75-80	<0.005	0.5	0.71	23	10	230	0.6	<2	5.64	5.1	17	28	90	4.54	<10	1	0.18	<10	2.45	586	16	0.01	81	560	6	1.95	9	11	207	<0.01	10	<10	146	<10	610					
LRC 06-17 80-85	<0.005	0.3	0.77	23	10	180	0.6	2	5.02	4	19	28	86	4.34	<10	<1	0.19	<10	2.43	547	13	0.01	72	490	7	1.84	7	11	212	<0.01	<10	<10	129	<10	486					
LRC 06-17 85-90	<0.005	0.2	1.6	23	20	190	0.8	<2	4.42	2.5	18	34	93	4.66	<10	<1	0.38	<10	2.47	525	11	0.02	79	450	9	1.82	<2	12	191	<0.01	<10	<10	128	<10	323					
LRC 06-17 90-95	0.007	0.3	1.87	22	20	190	0.8	<2	4.34	2.3	18	37	96	4.62	<10	<1	0.45	<10	2.48	506	9	0.02	78	450	8	1.89	2	13	186	<0.01	<10	<10	131	<10	309					
LRC 06-17 95-100	0.005	<0.2	1.61	24	20	200	0.7	<2	7.7	1.8	13	29	78	4.76	<10	<1	0.41	<10	3.72	665	7	0.02	61	400	6	1.81	<2	11	362	<0.01	<10	<10	116	<10	258					
LRC 06-17 100-105	<0.005	0.2	1.96	20	20	190	0.6	2	4.65	2.5	18	39	88	4.34	<10	<1	0.36	<10	2.38	512	8	0.02	59	450	7	1.8	2	11	207	<0.01	<10	<10	133	<10	311					
LRC 06-17 105-110	0.006	<0.2	1.83	15	20	160	0.6	<2	5.16	1.5	16	44	67	4.12	<10	<1	0.37	<10	2.58	579	5	0.02	67	540	7	1.4	<2	11	240	<0.01	<10	<10	97	<10	192					
LRC 06-17 110-115	0.005	0.2	1.61	16	20	180	0.7	<2	4.83	1.6	18	44	69	4.02	<10	<1	0.34	<10	2.47	575	6	0.02	66	430	8	1.46	3	12	251	<0.01	<10	<10	105	<10	239					
LRC 06-17 115-120	<0.005	<0.2	1.37	2	10	370	0.9	<2	7.24	0.6	27	85	105	5.34	<10	<1	0.29	20	3.5	895	2	0.03	62	1790	12	0.5	2	18	589	0.01	<10	<10	165	<10	139					
LRC 06-17 120-125	<0.005	<0.2	1.33	8	20	450	0.9	<2	6.87	0.7	26	77	95	4.82	<10	<1	0.29	10	3.39	800	3	0.03	52	1560	9	0.43	<2	15	644	0.01	<10	<10	148	<10	131					
LRC 06-17 125-130	<0.005	<0.2	1.24	<2	10	520	0.9	<2	8.18	<0.5	27	70	84	4.72	<10	<1	0.28	10	3.75	886	1	0.02	48	1480	6	0.27	<2	15	671	0.01	<10	<10	149	<10	88					
LRC 06-17 130-135	<0.005	<0.2	1.23	4	10	670	0.9	2	7.26	<0.5	25	77	102	5.11	<10	<1	0.36	20	3.58	948	1	0.03	46	1840	14	0.23	<2	19	612	0.01	<10	<10	165	<10	89					
LRC 06-17 135-140	<0.005	<0.2	1.17	<2	10	540	0.9	<2	8.41	<0.5	31	80	86	5.08	<10	<1	0.28	20	4.03	978	1	0.03	50	1520	9	0.18	2	17	604	0.01	<10	<10	165	<10	94					
LRC 06-17 140-145	<0.005	<0.2	1.59	8	20	360	0.9	<2	6.53	1.4	21	53	82	4.78	<10	<1	0.39	10	3.21	766	5	0.03	53	1020	11	0.96	2	14	494	0.01	<10	<10	133	<10	202					
LRC 06-17 145-150	<0.005	0.3	1.32	8	20	580	1.1	<2	7.64	0.9	25	60	98	5.42	<10	<1	0.44	20	3.66	985	3	0.03	45	1820	11	0.53	<2	17	640	0.02	<10	<10	148	<10	158					
LRC 06-17 150-155	<0.005	<0.2	1.42	<2	20	750	1.6	<2	9.15	0.5	32	88	106	6.09	<10	<1	0.56	30	4.35	1200	1	0.04	47	2310	16	0.14	<2	20	761	0.05	<10	<10	173	<10	103					
LRC 06-17 155-160	<0.005	<0.2	1.32	8	20	720	1.8	<2	7.74	<0.5	30	86	100	5.9	<10	<1	0.56	30	3.78	1120	1	0.04	46	2360	14	0.11	<2	21	726	0.05	<10	<10	165	<10	94					
LRC 06-17 160-165	<0.005	<0.2	1.21	2	10	710	1.4	<2	7.67	<0.5	30	83	101	6.03	<10	<1	0.55	20	3.69	1105	1	0.04	48	2220	13	0.22	<2	21	642	0.04	10	<10	175	<10	107					
LRC 06-17 165-170	<0.005	<0.2	1.62	4	20	490	1.2	<2	6.23	1.2	24	67	94	5.62	<10	<1	0.58	20	3.05	915	5	0.04	53	1730	11	0.93	4	18	493	0.02	<10	<10	155	<10	199					
LRC 06-17 170-175	0.005	0.2	1.55	16	20	190	1	<2	5.25	3.2	19	46	89	5.07	<10	<1	0.55	10	2.62	724	13	0.04	64	1340	9	1.54	6	15	410	0.01	<10	<10	138	<10	363					
LRC 06-17 175-180	0.006	0.3	1.09	18	20	130	0.7	<2	4.51	4	18	29	83	4.48	<10	<1	0.41	10	2.29	572	12	0.04	64	910	5	2.02	<2	12	329	<0.01	<10	<10	113	<10	435					
LRC 06-17 180-185	<0.005	0.3	1.32	16	30	140	0.7	<2	4.55	4.1	19	37	83	4.6	<10	1	0.47	10	2.23	662	11	0.04	72	1000	7	2.29	4	13	296	<0.01	<10	<10	113	<10	418					
LRC 06-17 185-190	0.006	<0.2	1.35	17	30	100	0.7	<2	3.98	2.7	18	34	77	4.39	<10	<1	0.49	10	2.01	583	10	0.04	73	840	6	2.14	4	12	292	<0.01	<10	<10	98	<10	313					
LRC 06-17 190-195	0.006	0.2	1.17	13	20	260	0.7	<2	5.14	2.1	14	25	70	4.32	<10	<1	0.42	10	2.34	655	9	0.04	62	710	9	1.86	<2	11	453	<0.01	<10	<10	81	<10	270					
LRC 06-17 195-200	<0.005	0.2	1.15	5	20	420	0.6	<2	5.16	0.9	13	46	55	3.21	<10	<1	0.33	10	2.17	605	4	0.05	45	970	7	0.53	<2	8	507	<0.01	<10	<10	82	<10	125					
LRC 06-17 200-205	<0.005	<0.2	1.29	4	20	340	0.8	<2	5.53	<0.5	18	65	80	4.03	<10	<1	0.37	10	2.41	732	4	0.05	48	1590	10	0.8	<2	11	654	<0.01	<10	<10	105	<10	112					
LRC 06-17 205-210	0.005	<0.2	1.1	9	20	280	0.6	<2	4.84	0.7	9	13	38	3.56	<10	<1	0.35	10	1.88	605	6	0.04	30	790	14	0.9	2	6	346	<0.01	<10	<10	53	<10	141					
LRC 06-17 210-215	0.006	<0.2	1.23	10	20	110	0.7	<2	4.04	1	10	19	48	3.32	<10	<1	0.44	10	1.53	507	8	0.05	51	620	14	1.18	<2	7	280	<0.01	<10	<10	52	<10	172					
LRC 06-17 215-220	0.007	0.2	1.13	11	30	360	0.7	<2	3.36	0.5	9	22	37	3.17	<10	<1	0.42	10	1.37	494	5	0.05	46	630	17	1.19	<2	7	205	<0.01	<10	<10	43	<10	120					
LRC 06-17 220-225	<0.005	<0.2	0.84	18	20	350	0.7	<2	3.64	0.7	16	15	42	3.87	<10	<1	0.3	10	1.92	529	8	0.05	58	790	16	1.08	<2	9	259	<0.01	<10	<10	51	<10	154					
LRC 06-17 225-230	0.005	<0.2	0.88	6	20	440	0.7	<2	4.72	<0.5	21	12	40	4.7	<10	<1	0.27	10	2.37	757	5	0.05	51	1130	11	0.93	<2	13	332	<0.01	<10	<10	64	<10	107					
LRC 06-17 230-235	<0.005	<0.2	0.64	6	20	370	0.6	<2	4	<0.5	11	14	37	3.15	<10	<1	0.25	10	1.47	518	8	0																		

VA06101108 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 91
 DATE RECEIVED : 2006-09-13 DATE FINALIZED : 2006-10-17
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE DESCRIPTION	Au	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn
	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	
LRC 06-17 460-465	<0.005	0.4	0.44	25	20	260	0.5	<2	4.95	1.6	10	19	51	3.4	<10	1	0.2	<10	2.47	494	27	0.08	94	230	10	1.58	<2	9	354	<0.01	<10	<10	57	<10	241
LRC 06-17 465-470	<0.005	<0.2	0.42	19	20	260	0.5	<2	6.21	1.3	10	25	51	3.09	<10	<1	0.19	<10	3.7	795	23	0.07	118	410	16	1.64	<2	7	432	<0.01	<10	<10	51	<10	203
LRC 06-17 470-475	<0.005	<0.2	0.4	16	20	300	0.5	<2	6	1	11	33	42	3.22	<10	<1	0.18	<10	3.64	614	20	0.07	147	220	10	1.41	<2	8	446	<0.01	<10	<10	46	<10	158
LRC 06-17 475-480	<0.005	<0.2	0.32	19	20	230	<0.5	<2	8.38	0.6	10	46	35	3.42	<10	1	0.15	<10	4.69	699	13	0.06	142	110	7	1.08	8	9	615	<0.01	<10	<10	56	<10	143
LRC 06-17 480-485	<0.005	0.3	0.45	20	20	270	0.6	<2	4.92	1.5	14	33	58	3.75	<10	<1	0.21	<10	2.85	503	17	0.08	151	130	11	1.59	5	10	357	<0.01	<10	<10	66	<10	262
LRC 06-17 485-490	<0.005	0.2	0.47	13	20	320	0.5	<2	4.62	1.8	9	24	43	3.14	<10	<1	0.19	<10	2.15	489	14	0.08	96	130	9	1.17	3	10	337	<0.01	<10	<10	64	<10	257
LRC 06-17 490-495	<0.005	0.2	0.47	20	20	240	0.6	<2	3.46	3.8	15	31	68	3.51	<10	1	0.23	<10	1.9	446	14	0.08	162	260	11	1.51	3	9	236	<0.01	<10	<10	71	<10	446
LRC 06-17 495-500	<0.005	0.4	0.51	14	30	230	0.7	<2	2.57	2	14	24	72	3.35	<10	1	0.25	<10	1.54	487	10	0.07	123	360	12	1.24	3	9	159	<0.01	<10	<10	59	<10	317

VA06101109 - Finalized
CLIENT : "SHK - Alpha Gold Corp."
of SAMPLES : 57
DATE RECEIVED : 2006-09-13 DATE FINALIZED : 2006-10-16
PROJECT : "Lust Dust"
CERTIFICATE COMMENTS : ""
PO NUMBER : ""

SAMPLE DESCRIPTION	Au	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn	
	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
LRC 06-19 35-40	<0.005	0.2	0.29	12	<10	50	<0.5	<2	>25.0	1.8	3	13	11	0.42	<10	3	0.02	<10	0.28	75	<1	0.01	11	140	6	0.05	5	2	153	0.01	<10	<10	11	<10	28	
LRC 06-19 40-45	<0.005	0.2	0.23	8	<10	30	<0.5	<2	>25.0	1.3	2	9	5	0.31	<10	6	0.03	10	0.16	48	<1	0.01	8	140	9	0.06	3	1	180	0.01	<10	<10	9	<10	41	
LRC 06-19 45-50	<0.005	<0.2	0.13	12	<10	20	<0.5	<2	>25.0	1.4	1	6	5	0.23	<10	6	0.02	10	0.11	29	<1	0.01	8	130	7	0.05	10	1	188	<0.01	<10	<10	7	<10	51	
LRC 06-19 50-55	<0.005	0.2	0.1	83	<10	70	<0.5	<2	>25.0	1.2	1	6	2	0.68	<10	11	0.01	10	0.1	22	1	0.01	7	210	6	0.06	52	1	166	<0.01	<10	<10	6	<10	56	
LRC 06-19 55-60	<0.005	0.3	0.1	130	<10	30	<0.5	<2	>25.0	1.6	2	7	3	0.72	<10	11	0.01	10	0.07	36	1	0.01	9	190	8	0.06	26	1	131	<0.01	<10	<10	7	<10	59	
LRC 06-19 60-65	<0.005	0.2	0.04	35	<10	10	<0.5	<2	>25.0	0.7	1	3	2	0.19	<10	3	<0.01	<10	0.07	26	<1	0.01	4	40	6	0.04	8	<1	147	<0.01	<10	<10	3	<10	29	
LRC 06-19 65-70	<0.005	0.2	0.04	51	<10	10	<0.5	<2	>25.0	0.7	2	3	1	0.23	<10	4	<0.01	10	0.09	22	<1	0.01	5	30	6	0.04	12	<1	171	<0.01	10	<10	2	<10	31	
LRC 06-19 70-75	<0.005	0.2	0.03	37	<10	10	<0.5	<2	>25.0	1.1	<1	3	1	0.16	<10	3	<0.01	10	0.08	18	<1	0.01	4	40	6	0.04	8	<1	171	<0.01	<10	<10	3	<10	26	
LRC 06-19 75-80	<0.005	0.2	0.06	26	<10	10	<0.5	<2	>25.0	1.3	<1	4	2	0.19	<10	6	<0.01	<10	0.09	41	<1	0.01	3	110	6	0.04	9	<1	138	<0.01	<10	<10	4	<10	25	
LRC 06-19 80-85	<0.005	0.4	0.16	27	<10	90	<0.5	<2	>25.0	2.1	2	4	4	0.3	<10	25	0.01	10	0.08	61	<1	0.01	12	370	11	0.06	17	1	127	<0.01	<10	<10	6	<10	69	
LRC 06-19 85-90	<0.005	0.4	0.15	22	<10	190	<0.5	<2	>25.0	2.1	2	5	3	0.25	<10	16	0.01	10	0.08	54	<1	0.01	10	360	11	0.08	14	1	141	<0.01	<10	<10	6	<10	58	
LRC 06-19 90-95	<0.005	0.2	0.06	18	<10	20	<0.5	<2	>25.0	1.5	1	3	2	0.15	<10	4	0.01	<10	0.09	53	<1	0.01	4	90	6	0.04	8	1	167	<0.01	<10	<10	4	10	33	
LRC 06-19 95-100	<0.005	0.2	0.04	10	<10	20	<0.5	<2	>25.0	0.7	<1	2	1	0.08	<10	3	<0.01	<10	0.1	40	<1	0.01	1	60	7	0.04	4	<1	179	<0.01	<10	<10	3	<10	18	
LRC 06-19 100-105	<0.005	<0.2	0.03	4	<10	10	<0.5	<2	>25.0	0.6	1	1	1	0.06	<10	3	<0.01	<10	0.09	29	<1	0.01	1	30	4	0.03	4	<1	165	<0.01	<10	<10	2	10	13	
LRC 06-19 105-110	<0.005	0.2	0.03	5	<10	10	<0.5	<2	>25.0	0.5	<1	1	1	0.05	<10	2	<0.01	<10	0.09	24	<1	0.01	2	50	6	0.03	4	<1	163	<0.01	<10	<10	2	<10	15	
LRC 06-19 110-115	<0.005	0.2	0.07	10	<10	20	<0.5	<2	>25.0	0.5	<1	3	3	0.11	<10	3	0.01	<10	0.11	33	<1	0.01	3	70	6	0.03	2	<1	167	<0.01	<10	<10	2	<10	23	
LRC 06-19 115-120	<0.005	<0.2	0.33	16	<10	70	<0.5	<2	>25.0	0.6	3	7	11	0.52	<10	4	0.02	<10	0.24	85	<1	0.01	11	130	7	0.04	9	1	164	0.02	<10	<10	13	<10	49	
LRC 06-19 120-125	<0.005	0.2	0.09	14	<10	20	<0.5	<2	>25.0	0.8	<1	4	3	0.16	<10	4	0.01	<10	0.12	71	<1	0.01	4	120	5	0.04	2	1	230	<0.01	<10	<10	5	<10	24	
LRC 06-19 125-130	<0.005	0.2	0.09	65	<10	10	<0.5	<2	>25.0	0.9	1	3	2	0.45	<10	13	0.01	10	0.08	56	<1	0.01	13	130	10	0.55	35	1	177	<0.01	<10	<10	4	<10	48	
LRC 06-19 130-135	<0.005	<0.2	0.13	94	<10	10	<0.5	<2	>25.0	1.2	2	4	3	0.61	<10	17	0.02	10	0.08	55	1	0.01	16	180	10	0.72	72	1	173	<0.01	20	<10	5	<10	70	
LRC 06-19 135-140	<0.005	<0.2	0.06	26	<10	10	<0.5	<2	>25.0	0.5	1	3	1	0.22	<10	5	0.01	<10	0.09	51	<1	0.01	4	160	7	0.17	24	1	193	<0.01	<10	<10	3	<10	18	
LRC 06-19 140-145	<0.005	0.2	0.04	82	<10	10	<0.5	<2	>25.0	0.6	<1	3	1	0.3	<10	6	<0.01	<10	0.08	37	<1	0.01	6	50	5	0.29	26	1	209	<0.01	<10	<10	3	<10	24	
LRC 06-19 145-150	<0.005	0.2	0.04	21	<10	10	<0.5	<2	>25.0	0.6	1	3	1	0.12	<10	6	<0.01	<10	0.08	35	<1	0.01	2	50	4	0.1	9	<1	225	<0.01	<10	<10	3	<10	16	
LRC 06-19 150-155	<0.005	0.2	0.04	24	<10	10	<0.5	<2	>25.0	0.5	<1	4	2	0.15	<10	3	<0.01	10	0.09	29	<1	0.01	2	30	6	0.14	11	<1	216	<0.01	<10	<10	3	<10	12	
LRC 06-19 155-160	<0.005	0.3	0.07	39	<10	20	<0.5	<2	>25.0	0.7	1	8	2	0.19	<10	5	0.01	10	0.09	53	<1	0.01	3	170	6	0.08	49	1	201	<0.01	<10	<10	5	<10	35	
LRC 06-19 160-165	<0.005	0.2	0.09	72	<10	20	<0.5	<2	>25.0	0.7	1	6	2	0.37	<10	7	0.01	<10	0.08	63	<1	0.01	6	150	8	0.34	44	1	181	<0.01	<10	<10	5	<10	33	
LRC 06-19 165-170	<0.005	0.2	0.09	71	<10	20	<0.5	<2	>25.0	0.6	1	5	2	0.47	<10	10	0.01	<10	0.1	60	<1	0.01	9	70	5	0.53	36	1	226	<0.01	<10	<10	5	<10	22	
LRC 06-19 170-175	<0.005	<0.2	0.11	134	<10	10	<0.5	<2	>25.0	0.5	1	5	2	0.82	<10	17	0.02	<10	0.09	70	<1	0.01	13	90	7	1	53	1	188	<0.01	10	<10	5	<10	29	
LRC 06-19 175-180	<0.005	0.2	0.15	96	<10	20	<0.5	<2	>25.0	1.3	1	6	3	0.63	<10	19	0.03	<10	0.07	44	1	0.01	17	120	9	0.77	52	1	204	<0.01	<10	<10	5	<10	41	
LRC 06-19 180-185	<0.005	<0.2	0.09	51	<10	10	<0.5	<2	>25.0	0.5	1	7	3	0.33	<10	6	0.01	<10	0.06	44	1	0.01	8	60	9	0.29	19	1	307	<0.01	<10	<10	5	<10	21	
LRC 06-19 185-190	<0.005	0.2	0.09	21	<10	10	<0.5	<2	>25.0	0.5	1	4	2	0.19	<10	3	0.01	<10	0.05	47	<1	0.01	5	60	4	0.13	8	1	312	0.01	<10	<10	4	<10	14	
LRC 06-19 190-195	<0.005	0.3	0.07	48	<10	10	<0.5	<2	>25.0	0.7	1	4	2	0.29	<10	4	0.01	<10	0.05	58	<1	0.01	5	50	5	0.28	16	<1	269	<0.01	<10	<10	3	<10	12	
LRC 06-19 195-200	<0.005	0.2	0.05	24	<10	10	<0.5	<2	>25.0	<0.5	<1	2	1	0.14	<10	4	0.01	<10	0.03	45	<1	0.01	2	40	3	0.16	6	<1	286	<0.01	<10	<10	2	<10	12	
LRC 06-19 200-205	<0.005	0.2	0.06	10	<10	10	<0.5	<2	>25.0	<0.5	<1	3	1	0.13	<10	1	0.01	<10	0.06	44	<1	0.01	5	50	2	0.09	7	<1	280	<0.01	<10	<10	3	<10	22	
LRC 06-19 205-210	0.006	0.5	0.13	24	<10	10	<0.5	<2	>25.0	<0.5	2	10	6	0.71	<10	3	0.03	<10	0.09	50	1	0.01	19	80	5	0.68	7	1	245	0.01	<10	<10	5	<10	33	
LRC 06-19 210-215	0.106	0.5	0.33	62	<10	30	<0.5	<2	16.6	1	10	10	14	1.48	<10	4	0.11	<10	0.11	53	1	0.01	112	240	17	1.68	21	2	141	0.01	<10	<10	11	<10	204	
LRC 06-19 215-220	0.013	0.5	0.17	22	<10	20	<0.5	<2	>25.0	0.7	2	12	5	0.45	<10	2	0.03	<10	0.12	58	2	0.01	14	90	9	0.23	5	1	221	0.01	<10	<10	7	<10	39	
LRC 06-19 220-225	<0.005	0.2	0.08	11	<10	10	<0.5	<2	>25.0	0.8	2	3	2	0.21	<10	1	0.01	<10	0.1	30	<1	0.01	4	40	6	0.13	6	1	211	<0.01	<10	<10	4	<10	23	
LRC 06-19 225-230	<0.005	0.2	0.08	9	<10	10	<0.5	<2	>25.0	<0.5	<1	7																								

VA06101370 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 93
 DATE RECEIVED : 2006-09-13 DATE FINALIZED : 2006-10-20
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE DESCRIPTION	Au-AA23 ppm	Au-GRA21 ppm	ME-ICP41 Ag ppm	ME-ICP41 Al %	ME-ICP41 As ppm	ME-ICP41 B ppm	ME-ICP41 Ba ppm	ME-ICP41 Be ppm	ME-ICP41 Bi ppm	ME-ICP41 Ca %	ME-ICP41 Cd ppm	ME-ICP41 Co ppm	ME-ICP41 Cr ppm	ME-ICP41 Cu ppm	ME-ICP41 Fe %	ME-ICP41 Ga ppm	ME-ICP41 Hg ppm	ME-ICP41 K %	ME-ICP41 La ppm	ME-ICP41 Mg %	ME-ICP41 Mn ppm	ME-ICP41 Mo ppm	ME-ICP41 Na %	ME-ICP41 Ni ppm	ME-ICP41 P ppm	ME-ICP41 Pb ppm	ME-ICP41 S %	ME-ICP41 Sb ppm	ME-ICP41 Sc ppm	ME-ICP41 Sr ppm	ME-ICP41 Ti %	ME-ICP41 Tl ppm	ME-ICP41 U ppm	ME-ICP41 V ppm	ME-ICP41 W ppm	ME-ICP41 Zn ppm
LRC 06-23 200-205	0.007		<0.2	0.02	<2	<10	10	<0.5	<2	>25.0	<0.5	<1	3	<1	0.05	<10	6	<0.01	<10	0.08	136	<1	0.01	1	180	<2	<0.01	<2	1	266	<0.01	<10	<10	1	<10	11
LRC 06-23 205-210	0.009		<0.2	0.02	3	<10	10	<0.5	<2	>25.0	<0.5	<1	3	<1	0.03	<10	2	<0.01	<10	0.09	43	<1	0.02	<1	270	<2	<0.01	<2	<1	252	<0.01	<10	<10	<1	<10	10
LRC 06-23 210-215	0.012		<0.2	0.02	4	<10	10	<0.5	<2	>25.0	<0.5	<1	3	<1	0.02	<10	2	<0.01	<10	0.09	25	<1	0.01	3	190	<2	<0.01	<2	<1	255	<0.01	10	<10	<1	<10	14
LRC 06-23 215-220	0.029		<0.2	0.02	11	<10	10	<0.5	<2	>25.0	<0.5	<1	3	<1	0.04	<10	2	<0.01	<10	0.1	27	<1	0.02	6	120	<2	<0.01	2	<1	270	<0.01	<10	<10	<1	<10	31
LRC 06-23 220-225	0.013		<0.2	0.03	2	<10	<10	<0.5	<2	5.9	<0.5	<1	1	1	0.19	<10	1	0.01	<10	0.02	16	<1	<0.01	2	30	<2	0.04	<2	<1	40	<0.01	<10	<10	<1	<10	2
LRC 06-23 225-230	0.154		<0.2	0.02	<2	<10	10	<0.5	<2	>25.0	<0.5	<1	3	<1	0.03	<10	<1	<0.01	<10	0.1	29	<1	0.01	3	130	2	<0.01	<2	<1	287	<0.01	10	<10	<1	<10	12
LRC 06-23 230-235	0.214		<0.2	0.03	<2	<10	10	<0.5	<2	>25.0	<0.5	<1	5	1	0.04	<10	3	<0.01	<10	0.11	20	<1	0.01	<1	260	<2	<0.01	<2	<1	316	<0.01	<10	<10	<1	<10	22
LRC 06-23 235-240	1.305		<0.2	0.03	5	<10	10	<0.5	<2	>25.0	<0.5	<1	4	2	0.1	<10	6	<0.01	<10	0.11	39	<1	0.01	2	140	<2	<0.01	4	<1	321	<0.01	<10	<10	1	<10	32
LRC 06-23 240-245	>10.0	46.9	0.5	0.03	2	<10	10	<0.5	<2	>25.0	<0.5	<1	4	3	0.07	<10	6	<0.01	<10	0.1	24	<1	0.01	3	230	<2	<0.01	3	<1	261	<0.01	<10	<10	<1	<10	29
LRC 06-23 245-250	7.16		<0.2	0.03	7	<10	10	<0.5	<2	>25.0	0.5	<1	4	4	0.05	<10	5	<0.01	<10	0.1	25	<1	0.02	3	320	<2	<0.01	6	<1	262	<0.01	10	<10	1	<10	34

VA06101372 - Finalized

CLIENT : "SHK - Alpha Gold Corp."

of SAMPLES : 103

DATE RECEIVED : 2006-09-13 DATE FINALIZED : 2006-10-19

PROJECT : "Lust Dust"

CERTIFICATE COMMENTS : ""

PO NUMBER : ""

SAMPLE	Au-AA23	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41
DESCRIPTION	Au ppm	Ag ppm	Al %	As ppm	B ppm	Ba ppm	Be %	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm			
LRC 06-21 415-420	0.005	<0.2	0.76	5	<10	170	<0.5	<2	1.03	<0.5	7	9	50	2.02	<10	<1	0.13	10	0.54	506	3	0.01	20	300	7	0.38	<2	2	117	<0.01	<10	<10	15	<10	59			
LRC 06-21 420-425	0.005	<0.2	0.71	6	<10	180	<0.5	<2	1.36	<0.5	5	13	45	1.88	<10	<1	0.11	<10	0.5	636	5	0.01	20	240	6	0.46	<2	2	144	<0.01	<10	<10	12	<10	55			
LRC 06-21 425-430	0.005	<0.2	0.71	6	<10	360	<0.5	<2	1.55	<0.5	5	8	39	1.57	<10	<1	0.11	<10	0.46	710	3	0.01	19	220	5	0.41	<2	2	135	<0.01	<10	<10	12	<10	50			
LRC 06-21 430-435	0.005	<0.2	0.57	6	<10	210	<0.5	<2	1.02	<0.5	5	7	39	1.43	<10	1	0.1	<10	0.36	514	3	0.01	18	260	4	0.53	<2	1	110	<0.01	<10	<10	9	<10	48			
LRC 06-21 435-440	<0.005	<0.2	0.63	8	<10	170	<0.5	<2	0.79	<0.5	6	9	49	1.55	<10	<1	0.11	<10	0.39	461	4	0.01	22	240	5	0.53	<2	1	80	<0.01	<10	<10	10	<10	51			
LRC 06-21 440-445	0.005	<0.2	0.67	7	<10	190	<0.5	<2	0.93	<0.5	6	12	51	1.78	<10	<1	0.12	10	0.43	496	5	0.01	23	250	7	0.61	<2	1	89	<0.01	<10	<10	11	<10	59			
LRC 06-21 445-450	<0.005	<0.2	0.72	6	<10	190	<0.5	<2	1.15	<0.5	6	9	53	1.75	<10	1	0.13	10	0.46	497	4	0.01	22	280	7	0.55	<2	1	115	<0.01	<10	<10	12	<10	58			
LRC 06-21 450-455	<0.005	0.2	0.81	6	<10	170	<0.5	<2	1.24	<0.5	7	10	52	1.89	<10	<1	0.12	10	0.51	522	4	0.01	22	290	7	0.49	<2	1	127	<0.01	<10	<10	13	<10	59			
LRC 06-21 450-455 DUF	0.006	<0.2	0.92	8	<10	190	<0.5	<2	1.14	<0.5	8	12	59	2.12	<10	1	0.14	10	0.57	525	5	0.01	25	330	8	0.58	<2	2	121	<0.01	<10	<10	16	<10	69			
LRC 06-21 455-460	0.032	<0.2	0.89	6	<10	150	<0.5	<2	1.37	<0.5	7	13	52	2.02	<10	<1	0.12	10	0.59	604	4	0.01	24	280	5	0.54	<2	2	135	<0.01	<10	<10	16	<10	59			
LRC 06-21 460-465	<0.005	<0.2	0.72	8	<10	180	<0.5	<2	0.87	<0.5	6	11	50	1.88	<10	<1	0.12	10	0.48	569	5	0.01	22	270	8	0.56	<2	1	80	<0.01	<10	<10	12	<10	60			
LRC 06-21 465-470	<0.005	0.2	0.53	6	<10	140	<0.5	<2	0.81	<0.5	5	7	46	1.52	<10	<1	0.09	<10	0.43	541	3	0.01	21	220	8	0.46	<2	1	69	<0.01	<10	<10	9	<10	50			
LRC 06-21 470-475	<0.005	<0.2	0.66	5	<10	180	<0.5	<2	0.75	0.5	5	10	58	1.68	<10	<1	0.12	10	0.46	434	4	0.01	24	240	14	0.53	<2	1	85	<0.01	<10	<10	12	<10	65			
LRC 06-21 475-480	0.01	<0.2	0.69	6	<10	190	<0.5	<2	0.88	<0.5	6	11	58	1.75	<10	<1	0.14	<10	0.47	373	4	0.01	23	290	10	0.72	<2	1	115	<0.01	<10	<10	12	<10	64			
LRC 06-21 480-485	<0.005	<0.2	1.02	6	<10	190	<0.5	<2	1.56	<0.5	8	16	58	2.22	<10	1	0.14	10	0.68	559	2	0.02	20	310	9	0.4	<2	2	171	<0.01	<10	<10	21	<10	60			
LRC 06-21 485-490	0.005	0.2	1.22	5	<10	180	<0.5	<2	1.94	0.5	10	19	58	2.72	<10	<1	0.13	10	0.85	691	3	0.03	23	480	10	0.52	<2	3	213	<0.01	<10	<10	32	<10	77			
LRC 06-21 490-495	<0.005	0.4	0.7	<2	<10	160	<0.5	<2	0.66	<0.5	5	10	45	1.71	<10	1	0.12	10	0.47	495	2	0.01	21	230	8	0.39	<2	2	79	<0.01	<10	<10	12	<10	53			
LRC 06-21 495-500	<0.005	0.2	0.71	<2	<10	160	<0.5	<2	0.6	<0.5	6	10	52	1.78	<10	<1	0.13	10	0.46	546	2	0.01	23	250	8	0.5	<2	1	72	<0.01	<10	<10	12	<10	60			
LRC 06-21 500-505	<0.005	0.3	0.76	4	<10	170	<0.5	<2	1.02	<0.5	7	13	52	2.01	<10	<1	0.13	10	0.53	594	4	0.01	23	320	9	0.61	<2	2	117	<0.01	<10	<10	16	<10	60			
LRC 06-21 500-505 DUF	<0.005	<0.2	0.73	2	<10	150	<0.5	<2	0.97	<0.5	6	12	49	1.85	<10	<1	0.12	<10	0.51	576	4	0.01	21	280	8	0.51	<2	2	114	<0.01	<10	<10	14	<10	58			

VA06106594 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 10
 DATE RECEIVED : 2006-10-23 DATE FINALIZED : 2006-11-06
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : ""
 PO NUMBER : ""

SAMPLE DESCRIPTION	Au-AA23 Au ppm	Au-AA23 Au Check ppm	Au-AA23 Au Check2 ppm	Au-GRA21 Au ppm
LRC 06-23 200-205	0.013			
LRC 06-23 205-210	0.021			
LRC 06-23 210-215	0.014			
LRC 06-23 215-220	0.715	0.275	0.081	
LRC 06-23 220-225	0.064	0.166	0.339	
LRC 06-23 225-230	0.634	1.83	2.62	
LRC 06-23 230-235	2.76	6.5	2.33	
LRC 06-23 235-240	1.61	1.375		
LRC 06-23 240-245	>10.0			28.6
LRC 06-23 245-250	4.48	>10.0		6.86

Appendix VIII

2006 Bedrock Trenching - ALS Chemex Certificates of Analysis

VA06055457 - Finalized

CLIENT : "SHK - Alpha Gold Corp."

of SAMPLES : 3

DATE RECEIVED : 2006-06-19 DATE FINALIZED : 2006-07-08

PROJECT : "Lust Dust"

CERTIFICATE COMMENTS : ""

PO NUMBER : ""

SAMPLE	Au-AA23	Au-GRA21	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	Zn-AA46		
	Au	Au	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn	Zn
DESCRIPT	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	%
M322421	3.16		26.5	0.08	>10000	<10	1180	<0.5	358	1.25	>500	6	35	677	43.8	<10	3	0.02	10	0.02	7960	25	<0.01	10	1960	1645	0.06	1265	1	36	<0.01	10	30	24	10	>10000	3.94
M322422	0.567		15.1	0.09	>10000	<10	270	<0.5	653	1.22	246	3	23	662	48.2	<10	11	0.03	<10	0.05	3050	22	<0.01	10	1390	1785	0.05	2920	1	26	<0.01	<10	20	53	10	>10000	3.02
M322423	>10.0	11.8	15	0.18	>10000	<10	1110	<0.5	181	1.66	>500	8	34	661	40.6	<10	8	0.09	10	0.03	8650	16	<0.01	<1	2630	707	0.02	1625	1	39	<0.01	10	30	18	<10	>10000	2.28

VA06076107 - Finalized
 CLIENT : "SHK - Alpha Gold Corp."
 # of SAMPLES : 21
 DATE RECEIVED : 2006-07-25 DATE FINALIZED : 2006-09-03
 PROJECT : "Lust Dust"
 CERTIFICATE COMMENTS : "OG62 methods used for overlimits due to high As."
 PO NUMBER : " "

SAMPLE	Au	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn	Ag-OG62	Pb-OG62	Zn-OG62	Ag-GRA21	
DESCRIP	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm		
M322425	0.235	9.8	0.32	2320	<10	170	<0.5	11	16.7	27.1	10	11	40	2.44	<10	<1	0.09	10	0.2	3440	3	0.01	21	430	1045	0.02	293	2	122	<0.01	<10	<10	14	<10	2480					
M322426	0.193	4.2	0.39	2530	<10	180	<0.5	4	4.45	20.1	5	29	51	2.64	<10	1	0.23	10	0.15	988	3	0.01	16	370	594	0.1	287	2	48	<0.01	<10	<10	14	<10	1910					
M322427	0.138	3.9	0.38	1865	<10	120	<0.5	3	6.48	38.6	3	11	27	2.5	<10	1	0.2	10	0.26	1100	3	0.01	13	250	689	0.09	426	2	43	<0.01	<10	<10	15	<10	2780					
M322428	0.028	1.1	0.14	2140	<10	80	<0.5	<2	>25.0	72.8	1	12	69	3.19	<10	<1	0.03	10	0.55	850	1	0.01	6	200	203	<0.01	964	1	293	<0.01	<10	10	22	<10	4050					
M322429	1.4	58.2	0.92	>10000	<10	280	0.5	86	1.12	299	<1	52	2330	36.3	<10	3	0.14	20	0.3	2170	9	0.01	19	1620	2610	0.07	2980	3	22	0.01	<10	10	106	30	>10000			2.73		
M322430	0.095	5.8	1.97	9640	<10	480	1.6	15	0.72	106	95	29	384	18.8	<10	3	0.16	40	0.18	10200	28	0.01	113	2890	101	0.01	513	7	21	<0.01	<10	10	78	10	>10000			1.6		
M322431	0.157	4.1	1.76	7390	<10	130	1.5	16	0.46	62.4	27	16	250	19.3	<10	1	0.14	50	0.09	1875	19	<0.01	98	1900	142	0.03	406	7	14	<0.01	<10	<10	50	10	>10000			1.22		
M322432	0.423	9.8	0.43	>10000	<10	120	<0.5	84	0.42	153	2	14	554	21	<10	6	0.14	20	0.05	840	14	0.01	22	1200	371	0.11	372	3	24	<0.01	<10	<10	31	<10	>10000			1.3		
M322433	1.5	>100	0.07	>10000	<10	170	<0.5	385	0.63	645	4	18	1610	21.5	<10	4	0.05	20	0.01	372	158	0.01	4	390	>10000	1.15	>10000	<1	23	<0.01	<10	70	12	40	>10000	>1500	22.3	1.14	2210	
M322434	4.16	13.4	0.06	>10000	<10	10	<0.5	119	0.13	539	<1	3	540	20.4	<10	3	0.04	<10	0.02	1075	<1	0.01	5	360	956	>10.0	1220	<1	6	<0.01	<10	<10	4	10	>10000			7.07		
M322435	4.91	24.9	0.04	>10000	<10	10	<0.5	289	0.23	378	<1	3	632	20.8	<10	3	0.02	<10	0.02	330	1	0.01	1	160	1775	>10.0	1415	<1	3	<0.01	<10	<10	4	10	>10000			4.65		
M322436	8.41	64.4	0.01	>10000	<10	10	<0.5	1125	0.04	38.3	<1	2	294	25.9	<10	5	0.01	<10	<0.01	17	2	0.01	<1	80	5610	9.03	4810	<1	4	<0.01	10	<10	1	<10	3510					
M322437	0.264	25.6	0.03	>10000	<10	60	<0.5	229	0.18	78.7	<1	7	217	9.42	<10	2	0.03	<10	0.03	540	1	0.01	<1	220	1910	1.49	1070	<1	12	<0.01	<10	<10	4	<10	4340					
M322438	0.901	56.7	0.03	>10000	<10	<10	<0.5	740	0.36	344	<1	6	1580	25.3	10	3	0.04	<10	0.05	610	2	0.01	<1	280	7750	>10.0	3330	<1	43	<0.01	<10	10	3	10	>10000			3.43		
M322439	0.359	18	0.47	>10000	<10	570	<0.5	77	2.04	197.5	3	33	1420	40.6	<10	2	0.06	30	0.16	11850	26	0.01	19	1820	700	0.15	2280	2	34	0.01	<10	10	40	20	>10000			2.17		
M322440	0.701	29.7	0.16	>10000	<10	210	<0.5	210	2.57	102	<1	27	835	44.9	<10	5	0.05	10	0.18	1465	28	0.01	11	2500	1855	0.37	3210	1	36	<0.01	<10	10	32	50	>10000			2.42		
M322441	3.88	77.7	0.26	>10000	<10	680	<0.5	2130	2.07	179	<1	24	588	35.8	10	9	0.15	10	0.12	2280	132	0.02	10	1980	9010	0.33	4940	2	222	0.01	<10	10	18	30	>10000			1.93		
M322442	5.67	34.8	0.05	>10000	<10	120	<0.5	332	4.73	151	<1	10	540	31.7	<10	4	0.04	10	0.29	2070	3	0.01	<1	430	2200	1.09	2330	1	85	<0.01	<10	10	10	<10	9860					
M322443	1.175	33.2	0.08	>10000	<10	200	<0.5	430	12.8	162.5	<1	14	547	19.9	<10	3	0.09	<10	1.55	1430	15	0.02	3	520	3560	0.57	2690	<1	143	<0.01	<10	10	18	<10	9340					
M322445	1.635	42.5	0.3	>10000	<10	260	<0.5	420	1.09	193.5	<1	32	1160	41.5	10	9	0.06	10	0.06	1250	41	0.01	5	1050	1710	0.12	3900	1	28	0.01	<10	10	33	30	>10000			1.67		
M322446	0.076	21.1	0.53	>10000	<10	300	<0.5	146	3.07	156.5	3	27	870	22.9	<10	8	0.16	10	0.71	1295	14	0.01	13	1330	1990	0.23	1980	2	55	0.01	<10	10	36	10	>10000			1.3		

SURFICIAL DEPOSITS

OB - Overburden

SUPERCrustal ROCKS

SPbh - Biotite Hornfels

LSm- Massive Limestone

LSI - Laminated Limestone

LSck - Calcite Knot Limestone

AP - Argillaceous Phyllite

SP - Siliceous Phyllite

MT - Mafic Tuff

LT - Lapilli Tuff

AT - Ash Tuff

INTRUSIVE ROCKS

M - Monzonite

Mp - Monzonite Porphyry

MD - Monzodiorite

D - Diorite

Fd - Felsite Dyke

Fpd - Felspar Porphyry Dyke

MODIFIERS

a - argillaceous

x - brecciated

m - mineralized

h - hematitic

c - chloritic

SECONDARY LITHOLOGIES - PRODUCTS OF ALTERATION AND MINERALIZATION

SKp - Prograde Skarn

SKpm - Mineralized Prograde Skarn


MS - Massive Sulphides

In-Depth Geological Services


ALPHA GOLD CORP.

Lustdust Project

2006 Cross Section Legend



PLAN




SECTION

Lust Dust Section 06-01

Left to Right - Cu Ag Au Trace Litho



SD=500a1 47550E 61464N 1300Elev

AZ=82 W-DIST=10



SCALE 1: 500

DATE	11 DEC 7	DRAWN		DESIGNED	
DWG No		DATAMINE		CHECKED	
				APPROVED	



Lust Dust Section 06-02



Left to Right - Cu Ag Au Trace Litho

SD=500a1 47510E 61560N 1300Elev

AZ=90 W_DIST=10

SCALE 1: 500

DATE	11 DEC 7	DRAWN	DESIGNED
DWG No	F=47400	DATAMINE	CHECKED
			APPROVED



Lust Dust Section 06-03

Left to Right - Cu Ag Au Trace Litho



SD=500a1 46980E 61762N 1227Elev

AZ=60 W_DIST=10


10 0 10 20 30 40 Metres

SCALE 1: 500


DATE	11 DEC 7	DRAWN	DESIGNED
DWG No		DATAMINE	CHECKED
			APPROVED



Lust Dust Section 06-04			
Left to Right - Cu Ag Au Trace Litho			
SD=500a1 47020E 61736N 1288Elev			
AZ=70 W_DIST=10			
SCALE 1 : 500			
DATE	11 DEC 7	DRAWN	DESIGNED
DWG N°	DATAMINE		CHECKED
			APPROVED




PLAN



SECTION

Lust Dust Section 06-05			
Left to Right - Cu Ag Au Trace Litho			
SD=500a1 47063E 61712N 1343Elev			
AZ=62 W-DIST=10			
SCALE 1: 500			
DATE	11 DEC 7	DRAWN	DESIGNED
DWG No		DATAMINE	CHECKED
			APPROVED



PLAN
SECTION



Lust Dust Section 06-06

Left to Right - Cu Ag Au Trace Litho

SD=500a1 46908E 61912N 1115Elev
AZ=69 W_DIST=15

SCALE 1: 500

DATE	11 DEC 7	DRAWN	DESIGNED
DWG No		DATAMINE	CHECKED
			APPROVED



Lust Dust Section 06-07



Left to Right - Cu Ag Au Trace Litho

SD=500a1 47397E 61653N 1326Elev



AZ=69 W-DIST=10

SCALE 1: 500


DATE	18 DEC 7	DRAWN		DESIGNED	
DWG No		DATUM		CHECKED	
				APPROVED	



Lust Dust Section 06-08			
Left to Right - Cu Ag Au Trace Litho			
SD=NONE 47397E		61651N 1321Elev	
AZ=112		W_DIST=10	
SCALE 1 : 500			
DATE	18 DEC 7	DRAWN	DESIGNED
DWG No		DATAM	CHECKED
			APPROVED



Lust Dust Section 06-09			
Left to Right - Cu Ag Au Trace Litho			
SD=500a1 47390E 61614N 1338Elev			
AZ=99 W_DIST=10			
SCALE 1: 500			
DATE	11 DEC 7	DRAWN	DESIGNED
DWC No	148	DATUM	CHECKED
			APPROVED



Lust Dust Section 06-10

Left to Right - Cu Ag Au Trace Litho


SD=500a1 47070E 61404N 1379Elev

AZ=90 W_DIST=10


10 0 10 20 30 40 Metres

SCALE 1: 500

DATE	11 DEC 7	DRAWN		DESIGNED	
DWG No		DATAMINE		CHECKED	
				APPROVED	




PLAN




SECTION
L=1700

Lust Dust Section 06-11			
Left to Right - Cu Ag Au Trace Litho			
SD=500a1 46993E 61384N 1465Elev			
AZ=90		W_DIST=10	
SCALE 1: 500			
DATE	11 DEC 7	DRAWN	DESIGNED
DWG No		DRAWN	CHECKED
		EXAMINE	APPROVED





PLAN



SECTION

Lust Dust Section 06-12			
Left to Right - Cu Ag Au Trace Litho			
SD=500a1 46989E 61435N 1423Elev			
AZ=90 W_DIST=10			
SCALE 1: 500			
DATE	11 DEC 7	DRAWN	DESIGNED
DWG No		DATUM	CHEKED
			APPROVED



000 0.1 0.1
 005 0.2 0.2
 010 0.3 0.3
 015 0.4 0.4
 020 0.5 0.5

1000	1.7	0.00
1005	1.8	0.00
1010	1.9	0.00
1015	2.0	0.00
1020	2.1	0.00
1025	2.2	0.00
1030	2.3	0.00
1035	2.4	0.00
1040	2.5	0.00
1045	2.6	0.00
1050	2.7	0.00
1055	2.8	0.00
1060	2.9	0.00
1065	3.0	0.00
1070	3.1	0.00
1075	3.2	0.00
1080	3.3	0.00
1085	3.4	0.00
1090	3.5	0.00
1095	3.6	0.00
1100	3.7	0.00
1105	3.8	0.00
1110	3.9	0.00
1115	4.0	0.00
1120	4.1	0.00
1125	4.2	0.00
1130	4.3	0.00
1135	4.4	0.00
1140	4.5	0.00
1145	4.6	0.00
1150	4.7	0.00
1155	4.8	0.00
1160	4.9	0.00
1165	5.0	0.00
1170	5.1	0.00
1175	5.2	0.00
1180	5.3	0.00
1185	5.4	0.00
1190	5.5	0.00
1195	5.6	0.00
1200	5.7	0.00
1205	5.8	0.00
1210	5.9	0.00
1215	6.0	0.00
1220	6.1	0.00
1225	6.2	0.00
1230	6.3	0.00
1235	6.4	0.00
1240	6.5	0.00
1245	6.6	0.00
1250	6.7	0.00
1255	6.8	0.00
1260	6.9	0.00
1265	7.0	0.00
1270	7.1	0.00
1275	7.2	0.00
1280	7.3	0.00
1285	7.4	0.00
1290	7.5	0.00
1295	7.6	0.00
1300	7.7	0.00
1305	7.8	0.00
1310	7.9	0.00
1315	8.0	0.00
1320	8.1	0.00
1325	8.2	0.00
1330	8.3	0.00
1335	8.4	0.00
1340	8.5	0.00
1345	8.6	0.00
1350	8.7	0.00
1355	8.8	0.00
1360	8.9	0.00
1365	9.0	0.00
1370	9.1	0.00
1375	9.2	0.00
1380	9.3	0.00
1385	9.4	0.00
1390	9.5	0.00
1395	9.6	0.00
1400	9.7	0.00
1405	9.8	0.00
1410	9.9	0.00
1415	10.0	0.00
1420	10.1	0.00
1425	10.2	0.00
1430	10.3	0.00
1435	10.4	0.00
1440	10.5	0.00
1445	10.6	0.00
1450	10.7	0.00
1455	10.8	0.00
1460	10.9	0.00
1465	11.0	0.00
1470	11.1	0.00
1475	11.2	0.00
1480	11.3	0.00
1485	11.4	0.00
1490	11.5	0.00
1495	11.6	0.00
1500	11.7	0.00
1505	11.8	0.00
1510	11.9	0.00
1515	12.0	0.00
1520	12.1	0.00
1525	12.2	0.00
1530	12.3	0.00
1535	12.4	0.00
1540	12.5	0.00
1545	12.6	0.00
1550	12.7	0.00
1555	12.8	0.00
1560	12.9	0.00
1565	13.0	0.00
1570	13.1	0.00
1575	13.2	0.00
1580	13.3	0.00
1585	13.4	0.00
1590	13.5	0.00
1595	13.6	0.00
1600	13.7	0.00
1605	13.8	0.00
1610	13.9	0.00
1615	14.0	0.00
1620	14.1	0.00
1625	14.2	0.00
1630	14.3	0.00
1635	14.4	0.00
1640	14.5	0.00
1645	14.6	0.00

Lust Dust Section 06-13a


Left to Right - Cu Ag Au Trace Litho

SD=500a1 46892E 62228N 1212Elev

AZ=49 W_DIST=10


SCALE 1 : 500

DATE	18 DEC 7	DRAWN	DESIGNED
DWG No		DATAMOVE	CHECKED
			APPROVED



SECTION

Lust Dust Section 06-13B			
Left to Right - Cu Ag Au Trace Litho			
SD=NONE 46892E		62228N 910Elev	
AZ=49		W_DIST=10	
SCALE 1: 500			
DATE	18 DEC 7	DRAWN	DESIGNED
DWG No		DATAM	CHECKED
			APPROVED



Lust Dust Section 06-14


Left to Right - Cu Ag Au Trace Litho

SD=500a1 49246E 61309N 900Elev


AZ=90 W-DIST=10

SCALE 1: 500

DATE	18 DEC 7	DRAWN		DESIGNED	
DWG No		DATAMINE		CHECKED	
				APPROVED	



PLAN



SECTION

Lust Dust Section 06-15

Left to Right - Cu Ag Au Trace Litho

SD=500a1 49554E 59750N 900Elev
AZ=90 W_DIST=15

SCALE 1: 500

DATE	19 DEC 7	DRAWN	DESIGNED
DWG No		DATAMINE	CHECKED
			APPROVED