

**TITLE DIVISION, MINERAL TITLES
VICTORIA, BC**

DEC 17 2007

KUKUT PROJECT

RECEIVED


DEC 20 2007

**Gold Commissioner's Office
VANCOUVER, B.C.**

VANCOUVER ISLAND BRITISH COLUMBIA

NANAIMO M.D

MAP 92E.090
TIN 7
LAT. 49° 52' LOG. 126° 9'



PREPARED BY

SPECOGNA MINERALS CORP

Nanaimo B.C.
October 2007

**TECHNICAL
Prospecting report by
Efrem Specogna**

TECHNICAL Prospecting report by Efrem Specogna

INDEX

Summary

History

Location and claim Tin 7 map

Access and Prospect

Geology

Location of showing map

Conclusion

Location of samples map

Location of other samples

Description of samples

Statement of cost

Statement of qualifications

Assays certificates

SUMMARY


The Tin property, Vancouver Island B. C. of the Specognas Kukut project is host of a unique known Tin and U. associated with it occurrence for Van Isle B.C., .hosted by a Paleo limestone the which is also host of low grade base metals, and a couple Km . down stream basic to ultra basic rock formation is host to Cu., Ni Pt., and Pd., .

History

The Province of British Columbia Ministry of Energy Mines and Petroleum Resources conducted a Stream SEDIMENT and WATER Geochemical AREA.in 1988. In the GOLD RIVER AREA map N 49'50 /16 E at the bottom of the CYPRESS Cr. Sample N' 881171 returned Ag 1.5 Cr 860 Cu 60 Co 34 Ni 80 Pb 80 Zn 188 Sn 140 ppm.

The TIN values is greater than the EXPLOITED ALLUVIAL PLACERS according to the Macropardia Encyclopedia Britannica .Several years ago Specogna located a Cu Ni occurrence in the Cypress Cr , as values were low for the time interest was lost but with recent high prices an overview was warranted and noticing the Sn high the SOURCE HAS BEEN LOCATED.

Internet Mapping Framework



This map is a user generated static output from an Internet mapping site and is for general reference only. Data layers that appear on this map may or may not be accurate, current, or otherwise reliable. THIS MAP IS NOT TO BE USED FOR NAVIGATION.



Legend

- Indian Reserves
- National Parks
- Parks
- Mineral Titles Grid (LRDW)
- Mineral Tenures (Mineral - LRDW)
- Mineral Claim
- Mineral Lease
- Reserves (Mineral - LRDW Sites)
- Placer Claim Designation
- Placer Lease Designation
- No Staking Reserve
- Conditional Reserve
- Release Required Reserve
- Surface Restriction
- Recreation Area
- Others
- Mining Division (MTO)
- Integrated Cadastral Fabric
- Survey Parcels
- BCGS Grid
- Contours (1:250K)
- Contour - Index
- Contour - Intermediate
- Areaof Exclusion
- Areaof Indefinite Contours
- Annotation (1:20K)
- Transportation - Points (TRIM)
- Helipad
- Transportation - Lines (TRIM)
- Airfield
- Airport
- Airstrip



Scale: 1:20,704

CYPRESS Creek. MAP 92E.090

Access

Is via Cypress main to M-16 H then approximately..1Km up this branch.


PROSPECT

A Paleo limestone not mapped is located in the Cypress cr. Area. It outcrops for 100 m. south north (HERE IT IS INTRUDED BY SEVERAL DYKES OF DIFFERENT COMPOSITION) and 700 m. east west ,on the western side is in contact with sediments .In this sulfide free area marble assays up to 160 ppm Tin and 80 ppm U .At elevation of 1839 on the southeastern corner of the limestone outcrop at UTM 49'50.064N 126'09.802W the limestone has been silicified and quartz veined .The veins assay up to Ag15 -Pb.4200 -Zn.-1520. Bi30.83.-Se.21.6 -Te.0.69.ppm.--Hg.3173 ppb .two samples of altered limestone returned 500 and 320 ppm Sn. respectively a MANTO ? OR REPLACED SICKER SULFIDES . In a small cr. 20 meters to the east of the veins Island Intrusion is exposed in between it and veins ground is covered. This TIN occurrence has similarities to the HINLU ORE FIELDS of SOUTHERN CHINA.

GEOLOGY

The Geology in the Cypress area is complex .Rocks are first exposed approx. one Km. up cr. on the southern side are mostly gabbroic at the which first outcrop in the Cypress Cu, Co. Ni. showing is located , here petrographic description of rocks bearing the mineralization is altered basic to ultra basic LAMPROPHYRE . On the northern side are mostly Island Intrusion .2.5 Km. further west on the south side a PALEO LIMESTONE that which has been intruded by several dikes of different composition and age is well exposed .On the northern side a limited SICKER is represented LEUCOCRATIC DIKETS COMPOSED MOSTLY of PLAGIOCLASE and QUARTZ have been introduced in most rocks .except the limestone and limited to Sicker .Here huge boulders net veined by island intrusive derived probably from top of rock bluff . At the elevation of 2608 feet ,N49.50,857--E 126.08,955 ,and 700 east of here ,some rocks have been altered to Serpentinite. lesser altered are several centimeters .large flakes of PHLOGOPITE bearing . This rocks are barren but at the base could be mineralized as described in test books .Further west rock are mostly volcanic. of different composition .


Across the Cypress from limestone , high up in a rock bluff, Cu stains are well visible and in same rock bluff to the west , a deeply oxidized GOSSAN is exposed. This rock bluff is at least one Km. long from east to west .the collapsing must have occurred after the glacial retreat .



Showing
Scale, 1:1000


CONCLUSION

A close spaced sampling after exposing the showing by stripping will tell the story. .Or two hundred forty m. of N Q D ,Drilling in three eighty m. holes fan' out from same position this to get a quick appraisal and minimize environmental disturbance .The gossans need to be sampled as it , most likely is a capping that could be TIN and most likely occurs in limestone, also the rock bluff need prospecting , it is very rough , do to the collapsing of the rock bluff in huge boulders., over a length of one Km. This occurrence might be unique ,but tin deposits usually occur in clusters . The Tin Uranium occurrence on the western side of the limestone outcrop needs a vertical hole to reach past the bottom of limestone as in most occurrences this is were the high grade occurs .



* MAIN SHOWING
UTM49'50.06N -126'09.802W

MAP 92E.090
SCALE.1:5000



DESCRIPTION of SAMPLES

T 1 silt 2 certificates
T 2 gabbroic granite
T 3 altered limestone
T-4 gneiss across Cypress from limestone
T 5 altered limestone
T 6 pegmatite biotite granite
D 1 granite
D 2 granite & gabbro
E 1 siliceous limestone
E 2 greenstone dyke in limestone
E 3 limestone and granite dyke
E 4 as above
F 1 ultra basic and dikets
F 2 altered sicker
N 1 top of limestone
N 2 limestone 70 m. dawn road
N 3 limonitic dike in sicker sediments
W 1 mostly volcanic with dikets
W 2 as above no dikets
7 K 1 2 3 altered ultrabasic with dikets
7 K 4gabbro
AK1 pinkish limestone float with two centimeter. round Garnets
from norgate cr.
AK2 limestone altered and contaminated by basic fluid
AK3 vein specs of galena 3 certificates
K1 vein with galena specs
K2 near vein
K3silicius contact with granitic dike
K4 limestone most west
K 5 basic to ultra basic
K6 gabbro
K 7ultrabKasic
K8.schit

STATEMENT of EXPENSES KUKUT PROGET

Then days prospecting two men	\$3,000
Truck \$100 per day	.1.000
Assays	1.325
Report	1200
Total	-----
	6.525

Prospecting in B.C. over several years I optioned new targets to most major Canadian and several Foreign companies.

Efrem Specogna

A handwritten signature in black ink, appearing to read "Efrem Specogna".

Efrem Specogna

Attention:

Project:

Sample type:

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 6V2192SJ


Date : Oct-18-06

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Tl %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
1	<0.2	1.35	<5	55	<0.5	<5	0.53	<1	15	19	22	3.80	<1	0.05	<10	0.58	564	2	0.02	13	432	<2	0.04	<5	3	15	<5	0.13	<10	10	122	<10	38	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

Company: **Efrem Specogna**
Project:
Attn:

6V-2192-SA1

Oct-18-06

We hereby certify the following assay of 1 soil sample
submitted Oct-10-06

Sample Name	Sn ppm
T 1	38
*DUP T 1	32
*MP-2	430
*BLANK	<1

Certified by

Efrem Specogna

Attention:

Project:

Sample type:

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 6V2162RL


Date : Oct-13-06

ICP-AES Whole Rock Assay

Lithium Metaborate Fusion

Sample Number	SiO ₂ %	Al ₂ O ₃ %	Fe ₂ O ₃ %	CaO %	MgO %	Na ₂ O %	TiO ₂ %	K ₂ O %	MnO %	P ₂ O ₅ %	LOI %	Ba ppm	Sr ppm	Zr ppm	Sc ppm	Y ppm	Be ppm	Co ppm	Cr ppm	Cu ppm	Ni ppm	V ppm	Zn ppm	Rb ppm	Nb ppm	Total %
T 2	51.81	16.72	9.62	8.65	7.41	1.95	0.64	0.91	0.15	0.07	1.71	383	328	113	24	13	<5	39	54	19	28	236	23	<100	15	99.74
T 3	35.72	2.67	1.40	46.53	0.94	0.22	0.13	0.10	0.10	0.08	10.60	18	401	19	<5	10	<5	<5	13	<5	9	31	19	<100	<10	98.53
T 4	62.29	16.63	5.52	3.50	2.44	3.57	0.58	2.41	0.15	0.13	1.17	583	216	120	14	18	<5	13	68	29	7	100	24	<100	<10	98.50

: Sample is fused with Lithium metaborate
and dissolved in dilute HNO₃.



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V6X 4R6
Tel: (604) 327-3438
Fax: (604) 327-3423

Assay Certificate

6V-2266-RA1

Company: **Efrem Specogna**

Oct-20-06

Project:

Alt:

We hereby certify the following assay of 2 rock samples
submitted Oct-17-06

Sample Name	Sn %
T 5	0.014
T 6	0.004
*DUP T 5	0.016
*MP-2	0.045
*BLANK	<0.001

Certified by



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

6V-2162-RA1

Company: **Efrem Specogna**

Oct-13-06

Project:

Attn:

We hereby certify the following assay of 3 rock samples
submitted Oct-04-06

Sample Name	Sn %
T 2	0.008
T 3	0.032
T 4	<0.001
*DUP T 2	0.009
*MP-2	0.043
*BLANK	<0.001

Certified by _____

Efrem Specogna

Attention:

Project:

Sample type:

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 6V2266RJ

Date : Oct-20-06

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Tb ppm	Tl %	Tl ppm	U ppm	V ppm	Wt ppm	Zn ppm	Zr ppm
T.5	<0.2	0.09	6	12	<0.5	<5	>13.00	<1	4	1	6	0.23	<1	<0.01	<10	0.02	719	5	<0.01	9	206	20	0.06	<5	<1	229	6	<0.01	<10	80	1	<10	16	1
T.6	<0.2	4.57	<5	23	<0.5	<5	2.43	<1	33	5	63	4.22	3	0.02	<10	1.96	390	<2	0.23	21	459	<2	0.19	<5	1	144	<5	0.06	<10	28	109	<10	35	1

A .5 gm sample is digested with 5 ml 3:1 HCl:HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Assay Certificate

6V-2338-RA1

Company: Efrem Specogna
Project:
Attn:

We hereby certify the following assay of 13 rock samples submitted Oct-24-06

Sample Name	Sn %
D1	0.005
D2	0.003
E1	0.005
E2	0.002
E3	0.003
E4	<0.001
F1	0.004
F2	0.003
N1	0.016
N2	0.014
N3	0.008
W1	0.011
W2	0.005
*DUP F1	0.004
*DUP N2	0.012
*MP-2	0.043
*BLANK	<0.001

Certified by

A handwritten signature in black ink, appearing to read "Sh".

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 6V2338RJ

Date : Nov-02-06

Efrem Specogna

Attention:

Project:

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
E1	3.5	0.57	10	<10	0.8	<5	1.90	15	4	83	69	0.59	1	<0.01	10	0.18	1361	3	0.01	15	468	723	0.05	12	1	11	<5	0.03	<10	<30	15	<10	717	5
N1	<0.2	0.63	15	174	<0.5	<5	>15.00	1	1	7	39	0.24	1	0.01	<10	0.06	1784	8	0.03	15	523	3	0.03	<5	<1	204	13	0.03	<10	48	5	<10	18	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada**Efrem Specogna**

Attention:

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Report No : 6V2338RL

Project:

Tel: (604) 327-3436 Fax: (604) 327-3423

Date : Nov-02-06


Sample type:

ICP-AES Whole Rock Assay

Lithium Metaborate Fusion

Sample Number	SiO ₂ %	Al ₂ O ₃ %	Fe ₂ O ₃ %	CaO %	MgO %	Na ₂ O %	K ₂ O %	TiO ₂ %	P ₂ O ₅ %	MnO %	BaO %	Cr ₂ O ₃ %	LOI %	Total %	C %	S %
F1	54.67	14.67	9.89	8.00	5.48	2.72	0.84	1.93	0.20	0.16	0.05	0.03	1.04	99.66	0.02	0.02
F2	71.77	13.69	2.05	1.96	2.05	0.81	2.47	0.30	0.05	0.07	0.09	0.01	3.14	98.48	0.20	0.07

These elements are not included in the total column: C, S

Sample is fused with Lithium metaborate
and dissolved in dilute HNO₃.

GEOCHEMICAL ANALYSIS CERTIFICATE

Specogna, Lucia File # A608384 (a)
1704 Centenary Drive, Nanaimo BC V9X 1A3 Submitted by: Lucia Specogna

SAMPLE#	Mo	Cu	Pd	Zn	Ag	Wt	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Tl	B	Al	Nb	K	H	Sc	Tl	S	Mg	Se	Te	Ge	
	ppm	ppm	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppb	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	-			
G-1	.60	4.03	2.56	44.5	14	3.4	4.2	528	1.76	.7	2.7	1.0	3.8	50.4	.01 < .02	.06	35	.49	.073	6.0	9.0	.58	192.6	.112	<1	.90	.055	.46	.2	1.7	.34 < .01	<5	.1 < .02	4.4				
A K1	10	6.80	30.35	8.2	71	4.0	1.1	1204	.18	3.7	2.0	1.0	.4	229.5	.42	.20	.02	227.75	.036	6.4	1.4	.03	8.7	.012	250	.41	.003 < .01	<1	1.1 < .02	<01	<5	.1 < .02	.6					
A K2	.58	5.42	8.11	6.7	28	<1	.3	646	.27	1.0	1.1	.7	.3	245.5	.50	.12	.02	228.78	.033	4.7	1.9	.04	7.2	.009	3	.77	.032	.01	<1	.5 < .02	< .01	<5	.3 < .02	1.4				
A K3	.15	4.47	4020.09	1751.4	15200	5.5	3.3	965	.38	<1	1.6	.6	1.0	15.0	41.74	.59	30.82	14	2.50	.055	6.9	16.8	.17	2.2	.026	1	.77	.002 < .01	<1	3	.8	.11	.15	3173	21.6	.69	1.6	
STANDARD DS7	20.88	106.21	68.38	414.7	855	56.1	9.3	645	2.49	51.1	4.8	100.4	4.4	77.7	6.34	5.76	4.47	86	.98	.082	13.7	254.5	1.09	383.3	.125	40	1.04	.103	.47	3.9	2.6	4.21	.22	204	3.5	1.12	5.1	

GROUP 1F30 - 30.00 GM SAMPLE LEACHED WITH 180 ML 2-2-2 HCl-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 600 ML, ANALYSED BY ICP/ES & MS.
(>) CONCENTRATION EXCEEDS UPPER LIMITS. SOME MINERALS MAY BE PARTIALLY ATTACKED. REFRACTORY AND GRAPHITIC SAMPLES CAN LIMIT AU SOLUBILITY.

- SAMPLE TYPE: ROCK R150

Data FA

DATE RECEIVED: NOV 10 2006 DATE REPORT MAILED: DEC 05 2006



Assayers Canada**Specogna Minerals Corporation**

Attention: Efrem Specogna

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 7V1672PL

Date : Aug-23-07

Project:

Sample type:

ICP-AES Whole Rock Assay

Lithium Metaborate Fusion

Sample Number	SiO ₂ %	Al ₂ O ₃ %	Fe ₂ O ₃ %	CaO %	MgO %	Na ₂ O %	K ₂ O %	TiO ₂ %	P ₂ O ₅ %	MnO %	BaO %	Cr ₂ O ₃ %	Be ppm	Co ppm	Cu ppm	Nb ppm	Ni ppm	Rb ppm	Sc ppm	Sr ppm	V ppm	Y ppm	Zn ppm	Zr ppm	LOI %	Total %	C %	S %
7K 1	50.14	16.80	8.10	8.11	8.94	2.29	1.07	0.23	0.06	0.14	0.03	0.01	<5	46	<5	<10	49	<100	8	400	87	5	54	38	3.37	99.37	0.01	0.04
7K 2	48.15	18.04	9.42	8.72	10.52	1.50	0.33	0.25	0.05	0.15	0.01	0.01	<5	57	5	<10	87	<100	9	411	82	5	56	25	2.79	99.99	0.03	0.10
7K 3	54.96	15.56	7.90	7.57	7.61	1.63	1.32	0.34	0.06	0.14	0.04	0.01	<5	42	<5	<10	59	<100	10	358	150	7	54	49	2.55	99.75	0.02	0.09
7K 4	48.17	13.77	13.98	11.29	7.52	1.50	0.17	1.80	0.15	0.20	0.01	0.03	<5	66	89	27	74	<100	42	426	434	23	92	86	0.29	99.01	0.01	0.02

These elements are not included in the total column: C, S

Sample is fused with Lithium metaborate
and dissolved in dilute HCl/HNO₃.

ACME ANALYTICAL LABORATORIES LTD.
(ISO 9001 Accredited Co.)

852 E. HASTINGS ST. VANCOUVER BC V6A 1R6

PHONE (604) 253-3158 FAX (604) 253-1716

GEOCHEMICAL ANALYSIS CERTIFICATE

Specogna, Lucia File # A608384 (b)
1704 Centenary Drive, Nanaimo BC V9X 1A3 Submitted by: Lucia Specogna

SAMPLE#	Cs ppm	Ge ppm	Hf ppm	Nb ppm	Rb ppm	Sn ppm	Ta ppm	Zr ppm	Y ppm	Ce ppm	In ppm	Re ppb	Be ppm	Li ppm	Pd ppb	Pt ppb	Sample gm
G-1	3.17	.1	.07	.49	38.0	.5	<.05	1.2	3.75	12.6	.02	1	.3	33.3	<10	<2	30
A K1	.02	<.1	.05	.04	.3	.1	<.05	1.6	7.87	5.8	<.02	2	.2	<.10	<2	<2	30
A K2	.19	<.1	.02	.02	.5	.2	<.05	.8	6.08	4.2	<.02	3	.1	.6	<10	<2	30
A K3	.03	.3	.10	.11	.1	.1	<.05	3.9	7.00	6.6	<.02	<1	.6	1.0	<10	2	30
STANDARD DS7	6.46	.1	.13	.66	37.4	5.2	<.05	5.8	5.52	39.3	1.56	6	1.7	29.6	83	42	30

GROUP 1F30 - 30.00 GM SAMPLE LEACHED WITH 180 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR, DILUTED TO 600 ML, ANALYSED BY ICP/ES & MS.
(>) CONCENTRATION EXCEEDS UPPER LIMITS. SOME MINERALS MAY BE PARTIALLY ATTACKED. REFRACTORY AND GRAPHITIC SAMPLES CAN LIMIT AU SOLUBILITY.

- SAMPLE TYPE: ROCK R150

Data FA

DATE RECEIVED: NOV 10 2006 DATE REPORT MAILED:..... DEC 05 2006



ACME ANALYTICAL LABORATORIES LTD.
(ISO 9001 Accredited Co.)

852 E. HASTINGS ST. VANCOUVER BC V6A 1R6 PHONE (604) 253-3158 FAX (604) 253-1716

GEOCHEMICAL ANALYSIS CERTIFICATE

Specogna, Lucia File # A608384R

1704 Centenary Drive, Nanaimo BC V9X 1A3 Submitted by: Lucia Specogna

AA
LL

SAMPLE#	Sn ppm
A K1	<1
A K2	<1
A K3	<1
STANDARD SO-18	13


GROUP 4B - REE - 0.200 GM BY L1802/L12B407 FUSION, ICP/MS FINISHED.

- SAMPLE TYPE: ROCK PULP

10-20-16 10:11:21 AM

Data FA

DATE RECEIVED: DEC 16 2006 DATE REPORT MAILED:.....



Specogna Minerals Corporation

Attention: Efrem Specogna

Project:

Sample type:

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 7V1672PL

Date : Aug-23-07

ICP-AES Whole Rock Assay

Lithium Metaborate Fusion

Sample Number	SiO ₂ %	Al ₂ O ₃ %	Fe ₂ O ₃ %	CaO%	MgO%	Na ₂ O%	K ₂ O%	TiO ₂ %	P ₂ O ₅ %	MnO%	BaO%	Cr ₂ O ₃ %	Be ppm	Co ppm	Cu ppm	Nb ppm	Ni ppm	Rb ppm	Sc ppm	Sr ppm	V ppm	Y ppm	Zn ppm	Zr ppm	LOI %	Total %	C %	S %
7K 1	50.14	16.80	8.10	8.11	8.94	2.29	1.07	0.23	0.06	0.14	0.03	0.01	<5	46	<5	<10	49	<100	8	400	87	5	54	38	3.37	99.37	0.01	0.04
7K 2	48.15	18.04	9.42	8.72	10.52	1.50	0.33	0.25	0.05	0.15	0.01	0.01	<5	57	5	<10	87	<100	9	411	82	5	56	25	2.79	99.99	0.03	0.10
7K 3	54.96	15.56	7.90	7.57	7.61	1.63	1.32	0.34	0.06	0.14	0.04	0.01	<5	42	<5	<10	59	<100	10	358	150	7	54	49	2.55	99.75	0.02	0.09
7K 4	48.17	13.77	13.98	11.29	7.52	1.50	0.17	1.80	0.15	0.20	0.01	0.03	<5	66	89	27	74	<100	42	426	434	23	92	86	0.29	99.01	0.01	0.02

These elements are not included in the total column: C, S

Sample is fused with Lithium metaborate
and dissolved in dilute HCl/HNO₃.

Activation Laboratories Ltd.

Report: A07-4296

Analyte Symbol	Au	Ag	Cu	Cd	Mo	Pb	Ni	Zn	S	Al	As	Ba	Be	Bi	Br	Ca	Co	Cr	Cs	Eu	Fe	Hf	Hg	Ir
Unit Symbol	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppb	
Detection Limit	2	0.3	1	0.3	1	3	1	1	0.01	0.01	0.5	50	1	2	0.5	0.01	1	2	1	0.2	0.01	1	1	5
Analysis Method	INAA	MULT INAA / TD- ICP	TD-ICP	TD-ICP	TD-ICP	TD-ICP	MULT INAA / TD- ICP	MULT INAA / TD- ICP	TD-ICP	TD-ICP	INAA	INAA	TD-ICP	TD-ICP	INAA	TD-ICP	INAA							
K1	<2	10.0	10	44.9	<1	2580	38	2000	0.17	1.55	13.5	<50	4	18	<0.5	6.68	13	30	<1	0.8	1.62	2	<1	<5
K2	<2	<0.3	48	0.7	<1	11	88	90	0.23	2.94	22.9	1050	<1	<2	<0.5	14.5	29	41	<1	0.6	1.96	<1	<1	<5
K3	33	<0.3	53	<0.3	1	7	10	22	<0.01	3.95	6.8	<50	<1	<2	<0.5	2.96	12	13	<1	0.6	2.11	<1	<1	<5
K4	<2	<0.3	4	0.7	<1	<3	35	48	0.05	2.20	7.3	460	<1	<2	<0.5	22.0	5	31	<1	0.7	1.38	<1	<1	<5
K5	<2	<0.3	38	<0.3	3	4	3	69	0.20	8.51	5.4	760	<1	<2	<0.5	5.43	29	9	<1	0.9	7.21	<1	<1	<5
K6	<2	<0.3	29	<0.3	3	<3	74	73	<0.01	5.89	<0.5	<50	<1	4	<0.5	8.04	48	146	<1	1.2	8.63	<1	<1	<5
K7	<2	<0.3	19	<0.3	2	<3	42	51	0.05	7.71	2.7	360	<1	5	<0.5	5.28	62	<2	<1	0.4	7.03	<1	<1	<5
K8	<2	<0.3	10	<0.3	<1	9	2	40	0.04	7.84	5.9	1430	1	<2	<0.5	1.84	<1	<2	<1	0.9	1.80	4	<1	<5
K9	<2	<0.3	52	<0.3	2	<3	45	49	0.11	9.96	24	<50	<1	7	<0.5	8.11	68	21	<1	<0.2	7.34	<1	<1	<5

Activation Laboratories Ltd.

Report: A07-4296

Analyte Symbol	K	Mg	Mn	Na	P	Rb	Sb	Sc	Se	Sr	Ta	Tl	Th	U	V	W	Y	La	Ce	Nd	Sm	Sn	Tb	Yb
Unit Symbol	%	%	ppm	%	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
Detection Limit	0.01	0.01	1	0.01	0.001	15	0.1	0.1	3	1	0.5	0.01	0.2	0.5	2	1	1	0.5	3	5	0.1	0.01	0.5	0.2
Analysis Method	TD-ICP	TD-ICP	TD-ICP	INAA	TD-ICP	INAA	INAA	INAA	INAA	TD-ICP	INAA	TD-ICP	INAA	INAA	TD-ICP	INAA	TD-ICP	INAA	INAA	INAA	INAA	INAA	INAA	
K1	0.03	1.45	5580	0.05	0.083	< 15	2.1	4.7	19	48	< 0.5	0.08	4.4	5.0	54	< 1	29	16.3	21	9	1.7	< 0.01	< 0.5	2.6
K2	0.62	1.01	985	0.21	0.042	33	0.4	7.4	< 3	116	< 0.5	0.15	1.6	2.9	79	< 1	20	11.1	14	< 5	2.0	0.05	< 0.5	1.8
K3	0.31	1.06	387	0.41	0.014	18	2.8	5.1	< 3	36	< 0.5	0.09	< 0.2	< 0.5	48	< 1	10	5.3	13	7	1.1	< 0.01	< 0.5	1.4
K4	0.09	0.81	1880	0.12	0.045	< 15	2.0	4.8	< 3	217	< 0.5	0.10	0.9	3.8	55	< 1	20	9.0	11	9	1.5	< 0.01	< 0.5	1.4
K5	1.42	2.55	1230	1.88	0.053	< 15	< 0.1	33.3	< 3	325	< 0.5	0.53	1.6	< 0.5	387	< 1	20	6.7	19	10	2.4	< 0.01	< 0.5	2.2
K6	0.15	3.50	1450	1.33	0.048	< 15	< 0.1	37.7	< 3	282	< 0.5	0.63	< 0.2	< 0.5	297	< 1	20	8.1	19	< 5	3.0	< 0.01	< 0.5	2.6
K7	0.46	5.23	1140	1.01	0.021	< 15	0.5	15.1	< 3	311	< 0.5	0.20	1.6	< 0.5	123	< 1	8	3.7	9	12	1.3	< 0.01	< 0.5	1.3
K8	2.68	0.88	482	1.89	0.028	79	0.5	5.2	< 3	327	< 0.5	0.10	6.3	2.9	21	< 1	11	15.1	31	< 5	2.1	< 0.01	< 0.5	2.8
K9	0.25	6.07	1280	0.88	0.021	< 15	< 0.1	14.3	< 3	331	< 0.5	0.18	< 0.2	< 0.5	144	< 1	6	2.8	6	< 5	0.9	< 0.01	< 0.5	0.9

Analyte Symbol	Lu	Mass
Unit Symbol	ppm	g
Detection Limit	0.05	
Analysis Method	InAA	InAA
K1	0.38	27.6
K2	0.29	22.0
K3	0.22	20.3
K4	0.22	20.0
K5	0.42	28.8
K6	0.44	28.1
K7	0.21	20.8
K8	0.42	22.7
K9	0.14	22.6

Activation Laboratories Ltd. Report: A07-4296

Quality Control																									
Analyte Symbol	Au	Ag	Ag	Cu	Cd	Mo	Pb	Ni	Ni	Zn	Zn	S	Al	As	Ba	Be	Bi	Br	Ca	Co	Cr	Cs	Eu	Fe	
Unit Symbol	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%		
Detection Limit	2	0.3	5	1	0.3	1	3	1	20	1	50	0.01	0.01	0.5	50	1	2	0.5	0.01	1	2	1	0.2	0.01	
Analysis Method	INAA	TD-ICP	INAA	TD-ICP	TD-ICP	TD-ICP	TD-ICP	TD-ICP	INAA	TD-ICP	INAA	TD-ICP	TD-ICP	INAA	INAA	TD-ICP	TD-ICP	INAA	TD-ICP	INAA	INAA	INAA	INAA		
GXR-1 Meas		30.0		1130	2.6	16	763	42		713		0.25	2.57			1	1380		0.86						
GXR-1 Cert		31.0		1110	3.30	18.0	730	41.0		760		0.257	3.52			1.22	1380		0.960						
DNC-1 Meas		< 0.3		96	< 1	7	251			50		0.06	10.7			< 1	6		7.37						
DNC-1 Cert		0.0270		96.0		0.700	6.30	247		66.0		0.0390	9.69			1.00	0.0200		8.06						
GXR-4 Meas		3.7		6490	< 0.3	302	50	42		71		1.68	7.20			2	18		0.97						
GXR-4 Cert		4.00		6520	0.860	310	52.0	42.0		73.0		1.77	7.20			1.90	19.0		1.01						
GXR-2 Meas		17.1		78	4.2	4	685	19		501		0.01	11.7			2	< 2		0.81						
GXR-2 Cert		17.0		76.0	4.10	2.10	690	21.0		530		0.0313	16.5			1.70	0.690		0.930						
SDC-1 Meas		< 0.3		28	< 0.3	< 1	25	34		93		0.06	8.12			3	< 2		0.99						
SDC-1 Cert		0.0410		30.0	0.0800	0.250	25.0	38.0		103		0.0650	8.34			3.00	2.60		1.00						
SCO-1 Meas		0.7		29	< 0.3	3	30	28		98		8.07				2	< 2		1.89						
SCO-1 Cert		0.134		28.7	0.140	1.37	31.0	27.0		103			7.24			1.84	0.370		1.87						
GXR-6 Meas		0.5		69	< 0.3	3	104	26		125		0.01	14.6			1	< 2		0.19						
GXR-6 Cert		1.30		66.0	1.00	2.40	101	27.0		118		0.0160	17.7			1.40	0.290		0.180						
OREAS 13P Meas				2210			2010																		
OREAS 13P Cert				2500			2260																		
DMMAS-104 Meas		223										< 50				1600	790			45	95		1.5	5.81	
DMMAS-104 Cert		229										96.2				1570	850			48.8	95.1		1.2	5.61	
K6 Orig		< 0.3		31	< 0.3	3	< 3	77		75		0.01	6.20			< 1	4		8.50						
K6 Dup		< 0.3		28	< 0.3	3	< 3	71		71		< 0.01	5.57			< 1	3		7.57						
K9 Split		< 2	< 0.3	< 5	52	0.3	< 1	3	45	< 20	49	< 50	0.12	10.1	2.4	< 50	< 1	7	< 0.5	6.15	68	21	< 1	0.5	7.46

Activation Laboratories Ltd. Report: A07-4296

Quality Control

Analyte Symbol	Hf	Hg	Ir	K	Mg	Mn	Na	P	Rb	Sb	Sc	Se	Sr	Ta	Ti	Th	U	V	W	Y	La	Ce	Nd	Sm	
Unit Symbol	ppm	ppm	ppb	%	%	ppm	%	%	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
Detection Limit	1	1	5	0.01	0.01	1	0.01	0.001	15	0.1	0.1	3	1	0.5	0.01	0.2	0.5	2	1	1	0.5	3	5	0.1	
Analysis Method	INAA	INAA	INAA	TD-ICP	TD-ICP	TD-ICP	INAA	TD-ICP	INAA	INAA	INAA	INAA	INAA	INAA	TD-ICP	INAA	INAA	TD-ICP	INAA	TD-ICP	INAA	INAA	INAA	INAA	
GXR-1 Meas					0.05	0.23	910	0.063												90	34				
GXR-1 Cert					0.0500	0.217	852	0.0650												80.0	32.0				
DNC-1 Meas					0.21	5.48	1080	0.027								137	0.25			157	19				
DNC-1 Cert					0.180	6.08	1150	0.0370								145	0.287			148	18.0				
GXR-4 Meas					3.83	1.63	157	0.115								214				86	15				
GXR-4 Cert					4.01	1.66	155	0.120								221				87.0	14.0				
GXR-2 Meas					1.26	0.79	854	0.063								150				57	14				
GXR-2 Cert					1.37	0.850	1010	0.105								160				52.0	17.0				
SDC-1 Meas					2.52	0.94	841	0.055								167	0.25			58	37				
SDC-1 Cert					2.72	1.02	883	0.0690								183	0.608			102	40.0				
SCO-1 Meas					2.22	1.55	393	0.086								196	0.25			128	24				
SCO-1 Cert					2.30	1.64	410	0.0900								174	0.380			131	28.0				
GXR-6 Meas					1.85	0.62	1100	0.040								42				189	15				
GXR-6 Cert					1.87	0.609	1010	0.0350								35.0				185	14.0				
Oreas 13P Meas																									
Oreas 13P Cert																									
DMMAS-104 Meas								3.52								6.7	14.4			8.0	70.2				
DMMAS-104 Cert								3.43								6.2	14.1			8.3	71.9				
K6 Orig					0.17	3.74	1530	0.048								278	0.53			268	23				
K6 Dup					0.13	3.28	1380	0.048								246	0.73			327	17				
K6 Split	< 1	< 1	< 5	0.24	6.10	1280	0.89	0.021	< 15	< 0.1	14.5	< 3	335	< 0.5	0.18	0.5	< 0.5	145	< 1	8	3.0	6	< 5	0.9	

Quality Control

Analyte Symbol	Sn	Tb	Yb	Lu	Meas
Unit Symbol	%	ppm	ppm	ppm	g
Detection Limit	0.01	0.5	0.2	0.05	
Analysis Method	INAA	INAA	INAA	INAA	INAA

GXR-1 Meas

GXR-1 Cert

DNC-1 Meas

DNC-1 Cert

GXR-4 Meas

GXR-4 Cert

GXR-2 Meas

GXR-2 Cert

SDC-1 Meas

SDC-1 Cert

SCO-1 Meas

SCO-1 Cert

GXR-6 Meas

GXR-6 Cert

OREAS 13P Meas

OREAS 13P Cert

DMMAS-104 Meas

DMMAS-104 Cert

K6 Orig

K6 Dup

K9 Split

3.4 0.50

3.0 0.4

< 0.01 < 0.5 0.9 0.14 27.8