BC Geological Survey
Assessment Report
29920

Report on Diamond Drilling
at the KSM (Kerr-Sulphurets-Mitchell) Property

Mineral Claims 254756, 254758, 516245, and 516251
Skeena Mining Division
NTS 104B08, 104B09
56.52°N, 130.25°W

Owned and Operated by
Seabridge Gold Inc.

Work performed
June 19 – November 6, 2007

Report by
Mike Savell (P. Geo.)

May 15, 2008

SEABRIDGE
GOLD INC.

TABLE OF CONTENTS

Text

page
INTRODUCTION 2
Location 2
Access 2
History 3
Economic and General Assessment 5
New Work 6
GEOLOGY AND DISCUSSION OF RESULTS 7
Regional Geology 7
Property Geology 7
Mitchell Zone Geology 9
Lithology 9
Alteration 10
Mineralization 11
Structure 12
2007 DRILLING CAMPAIGN 13
Collar Locations 13
Drilling Conditions 14
Drill Core Processing 15
Sample Preparation and Dispatch 16
Analytical Procedures 17
Quality Control Measures 17
STATEMENT OF COSTS 19
STATEMENT OF QUALIFICATIONS 20
Bibliography and References 21

Tables

Table 1: Exploration History of the Kerr Property……...……...…3
Table 2: Exploration History of the Sulphurets Property……...…….4
Table 3: Summary of Mineral Resource Estimates…….6
Table 4: 2007 Drill Hole Data……...14

Maps (follow text)

Location Map
Claim Map
KSM Property Geology
Mitchell Zone Plan Map
Geological Section 07
Geological Section 11
Geological Section 15
Geological Section 19

Appendices (follow maps)

Appendix 1: Drill Hole Logs
Appendix 2: Assay Tables
Appendix 3: Certificates of Analyses

INTRODUCTION

Location

The Kerr-Sulphurets-Mitchell (KSM) property is located in northwest British Columbia at a latitude and longitude of approximately 56.52ON and 130.25OW, about 950 kilometers northwest of Vancouver, 65 kilometers north-northwest of Stewart and 21 kilometers south-southeast of the Eskay Creek Mine. The property consists of 26 contiguous mineral claims that cover an area of about 6,626 hectares that are 100% owned by Seabridge Gold Ltd. Placer Dome Inc. (now Barrick Gold) retains a 1% net smelter royalty on the property that is capped at C$4.5 million. The 26 claims were converted from 58 older "legacy" claims to B.C.'s new Mineral Titles Online (MTO) system in 2005.

The property lies in the rugged Coastal Mountains of northwest British Columbia, with elevations ranging from 520 meters in Sulphurets Creek valley to over 2,300 meters at the highest peaks. Valley glaciers fill the upper portions of the larger valleys from just below tree line and upwards. The glaciers have been retreating for at least the last several decades. Aerial photos from 1991 indicate the Mitchell Glacier has retreated almost a kilometer laterally and perhaps several hundred meters vertically since then.

The property is drained by Sulphurets and Mitchell Creek watersheds that empty into the Unuk River, which flows westward to the Pacific Ocean through Alaska. Tree line lies at about 1,240 meters above sea level, below which a mature forest of mostly hemlock and balsam fir abruptly develops. Fish are not known to inhabit the Sulphurets and Mitchell watersheds. Large wildlife such as deer, moose, and caribou are rare due to the rugged topography and restricted access however bears and mountain goats are present
.
The climate is generally that of a temperate or northern coastal rainforest, with subarctic conditions at high elevations. Precipitation is high with annual rainfall and snowfall totals estimated to be somewhere between the historical averages for the Eskay Creek Mine and Stewart B.C. These range from 801 to 1,295 millimeters of rain and 572 and 1,098 centimeters of snow, respectively (data to 2005). The length of the snow-free season varies from about May through November at lower elevations and from July through September at higher elevations.

Access

Access to the property is via helicopter. For the 2007 drilling program, an Astar 350B2 was chartered from Lakelse Helicopters out of Terrace, B.C. Two staging areas for mobilizing crews and equipment were used. These are 1) an area located at kilometer 54 on the private Eskay Creek Mine Road, which is about 25 kilometers to the north-northwest of the property and 2) along the public Granduc Road, which is located about

35 kilometers to the south-southeast of the property, which in turn is about 40 kilometers north of the town of Stewart B.C. A section of this road passes through Alaska and the town of Hyder.

Stewart, a town of approximately 500 inhabitants, is the closest population center to the property. It is connected to the provincial highway system via paved, all weather highway (#37A). The larger population centers of Prince Rupert, Terrace, and Smithers, with a total population of about 32,000, are located approximately 270 kilometers to the southeast.

History

The modern exploration history of the area began in the 1960's, with brief programs conducted by Newmont, Granduc, Phelps Dodge, and the Meridian Syndicate. All of these programs were focused towards gold exploration. Various explorers were attracted to this area due to the numerous large, prominent pyritic gossans that are exposed in alpine areas. There is evidence that prospectors were active in the area prior to 1935. The Sulphurets Zone was first drilled by Esso Minerals in 1969; Kerr Zone was first drilled by Brinco in 1985; and Mitchell Zone by Newhawk Gold in 1991.

In 1989, a 100% interest in the Kerr property was acquired by Placer Dome from Western Canadian Mines and in the following year they acquired the adjacent Sulphurets property from Newhawk Gold Mines. The Sulphurets property also hosts the Mitchell zone and other mineral occurrences. In 2000, Seabridge Resources acquired a 100% interest from Placer Dome in both the Kerr and Sulphurets properties, subject to capped royalties.

There is no recorded mineral production, nor evidence of it, from the property. Immediately west of the property, small-scale placer gold mining has occurred in Sulphurets and Mitchell Creeks. On the Bruceside property immediately to the east and currently owned by Silver Standard Resources, limited underground development and test mining was undertaken in the 1990's on narrow, gold-silver bearing quartz veins at the West Zone.

Table 1: Exploration History of the Kerr Property

Year	Activity
1982-1883	"Alpha JV" began prospecting and soil geochem surveys of the Kerr gossan focusing on gold
1984-1985	Brinco optioned the Kerr project, completed some geologic surveys and drilled 3 holes
1987-1989	Western Canadian Mines optioned Kerr and completed 59 drill holes and recognized Cu-Au porphyry
1989	Placer Dome (Placer) acquires Kerr property
1990-1992	Placer began delineation drilling of Kerr deposit at 50m centers by drilling 82 holes

1992-1996	Placer estimated resources (non NI 43-101), met testwork, and scoping studies
1996-2000	Project was dormant
2000	Seabridge Gold acquired a 100% interest in Kerr from Placer Dome
2002	Noranda Inc. acquired an option from Seabridge with the right to earn up to a 65% interest in Kerr
2003-2004	Noranda Inc. undertook various exploration surveys
2006	Seabridge Gold purchases Falconbridge (formerly Noranda) option

Table 2: Exploration History of the Sulphurets Property

Year	Activity
1880-1933	Limited placer gold exploration and mining
1935-1959	Placer gold prospecting, prospecting and staking of mining claims
1959-1960	Newmont and Granduc conducted surveys including airborne mag. Sulphurets and Iron Cap Au zones discovered. D. Ross, S. Bishop and W. Dawson prospected and stake claims in area.
1961-1968	Granduc Mines conducted geologic/geochem surveys, drilled 9 holes into Sulphurets zone. Ross-Bishop-Dawson claims optioned by Phelps Dodge in '62, Meridian Syndicate in '65, and Granduc in '68.
1963	R. Kirkham completed a M.Sc. thesis on the geology of Mitchell and Sulphurets areas.
1981	T. Simpson completed a M.Sc. thesis on the geology of the Sulphurets gold zone.
1971-1977	Granduc Mines conducted additional exploration surveys targeting molybdenum & drilled 6 holes into Snowfield zone (Bruceside)
1979-1984	Esso Minerals optioned Sulphurets property and completed early stage exploration including drilling 14 holes (2275 meters).
1985-1991	Granduc optioned Sulphurets to Lacana (later Corona) and Newhawk Gold Mines. Lacana-Newhawk JV spends ~ $21M developing West Zone and other smaller precious metal veins on Bruceside property. Drilled 11 holes at Sulphurets. Homestake undertook exploration after acquiring Corona.
1991	Arbee prospect optioned by Newhawk from D. Ross.
1992	Arbee prospect optioned by Placer Dome from Newhawk.
1991-1992	Newhawk commissioned AB geophysical survey over Sulphurets. Newhawk subdivided Suphurets property into Sulphside and Bruceside. Placer Dome acquires Sulphside (Sulphurets, Mitchell, Iron Cap, and other
1992	Placer Dome undertook delineation drilling of Sulphurets deposit at 50 meter centers (23 holes).
1993	J. Margolis completed a PhD thesis on the Sulphurets district. Newhawk-Corona drilled 3 holes in the Snowfields and Josephine zones east of Sulphurets.

1992-1996	Placer Dome completed geologic modeling, resource estimation (not NI 43-101 compliant), preliminary met testwork, and scoping studies.
1999	Silver Standard Resources acquired Newhawk Gold Mines (Bruceside property).
1996-2000	Sulphurets project was dormant.
2000	Seabridge Gold acquired a 100% interest in Sulphurets from Placer Dome.
2002	Noranda Inc. acquired an option to earn up to 65% from Seabridge.
2003-2004	Noranda Inc. undertook various exploration surveys.
2005	Falconbridge Ltd. (formerly Noranda) completed 4,092 meters of diamond drilling in 16 holes.
2006	Seabridge Gold purchased Falconbridge's option and conducts drilling programs on Mitchell and Sulphurets deposits (9,098.8m in 29 holes, operated by Falconbridge).
2007	Seabridge Gold puchased Arbee prospect from D. Ross.

Economic and General Assessment

The property lies within an area known as “Stikinia”, which is a terrane consisting of Triassic and Jurassic volcanic arcs that were accreted onto the Paleozoic basement. Early Jurassic sub-volcanic intrusive complexes are scattered through the Stikinia terrane and are host to numerous precious and base metal rich hydrothermal systems. These include several well known copper-gold porphyry systems such as Galore Creek, Red Chris, Kemess, and Mt. Milligan.

The Mitchell Zone is underlain by foliated, schistose, volcanic and volcaniclastic rocks that are exposed through an erosional window below the shallow north dipping Mitchell thrust fault. These rocks tend to be highly altered (primarily phyllic and propylitic) and characterized by intense sericitization, abundant pyrite with numerous intense quartz vein stockworks and sheeted quartz veins that are often deformed and flattened. Gold and copper mineralization tends to be relatively low-grade but dispersed over a very large area and appears to be related to hydrothermal activity associated with Early Jurassic hypabyssal porphyritic intrusions. Most of the mineralization appears to be hypogene with the principal sulfides being pyrite and chalcopyrite with minor molybdenite and trace amounts of tennantite, bornite, sphalerite, and galena. Within the higher-grade core of the deposit, gold and copper grades tend to correlate well with one another. Preliminary work indicates that gold is intimately associated with chalcopyrite. Copper/gold ratios tend to be slightly higher near the phyllic-propylitic alteration contact zones. In low-grade areas, which tend to flank the higher-grade core, copper/gold ratios tend to be highest. In general, within the currently drilled area, gold and copper grades tend to be remarkably consistent between drill holes, which is consistent with a large, stable hydrothermal system with a low thermal gradient.

Using data from this and previous drilling programs, in late 2007 Seabridge commissioned Resource Modeling Inc. to estimate Mineral Resources for the Mitchell Creek zone by creating a three-dimensional block model. Gold and copper grades were estimated using 15-meter-long drill hole composites by inverse distance, ordinary kriging, and nearest neighbor methods. Table 1-1 summarizes the estimated global Mitchell Creek Indicated and Inferred Mineral Resources using a 0.50 g/t gold-equivalent cutoff grade. The gold equivalent grade was calculated using gold and copper prices of US$650 per ounce and US$2.00 per pound, respectively. In addition, gold and copper recoveries of 70% and 85% were used in the gold equivalency calculation, respectively. Updated resource estimates for the Kerr and Sulphurets zones are also included.

Table 3: Summary of Mineral Resource Estimates

KSM Mineral Resource Estimates at 0.50 g/t Equivalent Gold Cutoff Grade										
Zone	Indicated Mineral Resources					Inferred Mineral Resources				
	Tonnes (000)	Gold (g/t)	Copper (%)	Gold Ounces (000)	Copper Pounds (millions)	Tonnes (000)	Gold (g/t)	Copper (%)	Gold Ounces (000)	Copper Pounds (millions)
Mitchell	734,163	0.69	0.18	16,287	2,913	667,421	0.62	0.15	13,304	2,206
Kerr	206,272	0.25	0.45	1,651	2,037	51,387	0.21	0.45	352	506
Sulphurets	74,655	0.75	0.24	1,798	388	33,636	0.62	0.20	675	147
Total	1,015,090	0.61	0.24	19,736	5,338	752,444	0.59	0.18	14,331	2,859

The KSM project represents one of the world's largest undeveloped gold/copper projects.

In March 2008, Seabridge Gold submitted a Project Description for KSM to the B.C. Government. The issuance of a Section 10 Order under the BC Environmental Act on April 25, 2008 formally launches the KSM Project into the British Columbia environmental review process. The Project Description Document envisages a large tonnage operation in the range of 80,000 to 120,000 metric tonnes per day of ore fed to a flotation mill which would produce a combined gold/copper/silver concentrate for transport by truck or pipeline to the nearby deep-sea port of Stewart. Combining production of all the resources from the Kerr, Sulphurets and Mitchell zones could sustain a mine life in excess of 30 years at this envisaged throughput rate. Preliminary open pit plans suggest a waste-to-ore strip ratio of 0.3 to 1 during the initial 10 years of production from the Mitchell zone, increasing to an overall life-of-mine average of 1.35 to 1 for all three zones combined.

New Work

This report documents Seabridge's 2007 drilling program. In 2007, all drilling at the KSM project was undertaken within and peripheral to the Mitchell zone. A total of 15,294 meters of core drilling in 37 holes were completed. All holes were logged for geological and geotechnical attributes, photographed, split and assayed at an average interval of 2 meters. Most of the core is stored in cross-stacked piles near the camp on

the property. Selected intervals of holes M-07-24, 25, 26, 28, 29, 30, 31, 35, 37, 42, and 55 are stored on a lot owned by Seabridge Gold Inc. in Stewart.

GEOLOGY AND DISCUSSION OF RESULTS

Regional Geology

The region lies within "Stikinia", a terrane of Triassic and Jurassic volcanic arcs that were accreted onto the Paleozoic basement of the North American continental margin in the Middle Jurassic. Stikinia is the largest of several fault bounded, allochthonous terranes within the Intermontane belt, which lies between the post-accretionary, Tertiary intrusives of the Coast belt and continental margin sedimentary prisms of the Foreland (Rocky Mountain) belt. In the Kerr-Sulphurets area, Stikinia is dominated by variably deformed, oceanic island arc complexes of the Triassic Stuhini and Jurassic Hazelton groups. Back-arc basins formed eastward of the property in the Late Jurassic and Cretaceous were filled with thick accumulations of fine black clastic sediments of the Bowser Group. Folding and thrusting due to compressional tectonics in the late Cretaceous generated the area's current structural features. Remnants of Quaternary basaltic eruptions occur throughout the region.

Early Jurassic sub-volcanic intrusive complexes are common in the Stikinia terrane, and several host well-known precious and base metal rich hydrothermal systems. These include copper-gold porphyry deposits such as Galore Creek, Red Chris, Kemess, Mt. Milligan, and KSM. In addition, there are a number of related polymetallic deposits including skarns at Premier, epithermal veins and subaqueous vein and replacement sulfide deposits at Eskay Creek, Snip, Bruceside, and Granduc.

Property Geology

At KSM, Triassic rocks include marine sedimentary and intermediate volcanic rocks of the Stuhini Group. The lowermost Stuhini Group is dominated by turbiditic argillite and sandstone, which are overlain by pillowed volcanic flows and breccias. The upper portion consists of turbidites and graded sandstones similar to the base strata. The Stuhini Group is separated by an erosional unconformity from the overlying Jurassic sediments and volcanics of the Jack Formation and Hazelton Group. The Jack Formation is comprised of fossiliferous limey mudstones and sandstones. The base is marked by a granodiorite and limestone cobble bearing conglomerate. Overlying the Jack Formation is the Hazelton Group, dominated by andesitic flows and breccias deposited in a volcanic chain with high paleotopographic relief. Distinct felsic welded tuff horizons of the Mount Dilworth Formation are an important stratigraphic marker in the Hazelton Group, as they are closely associated with the Eskay Creek deposit.

A variety of dikes, sills, and plugs of diorite, monzodiorite, syenite, and granite are found in the area. Radiometric dating indicates these are of Early Jurassic age and they are collectively referred to as the “Mitchell Intrusions”. Below the Sulphurets and Mitchell thrust faults, pre- and intra-mineral intrusives have historically been very difficult to differentiate due to intense hydrothermal alteration. Above the faults there are a number of sills and plugs of coarse-grained feldspar porphyritic monzonite to low-silica granite that intruded siliceous sedimentary and volcanic rocks. Copper and gold mineralization is typically best developed at the margins of these intrusions. There appear to be both pre-, intra-, and post-mineral phases of mineralization.

The alteration zones and associated mineralization have been subjected to low greenschist facies metamorphism along with folding and faulting. In addition, a pre-Jurassic orogenic event imparted at least an equivalent metamorphic grade on the Triassic rocks. The Sulphurets and Mitchell thrust faults are interpreted to have placed Triassic Stuhini Group volcanics and sediments over Jurassic Hazelton Group rocks during a southeast vergent, compressive event during the Cretaceous. The displacement is not considered to be significant, as panels above and below the faults are altered and mineralized by the same intrusive event. Alteration and mineralization styles are distinct, with the upper plates containing a higher proportion of intrusive rock, potassic alteration and a higher copper to gold ratio, consistent with deeper parts of a copper porphyry system. The lower plate or plates, which host the Kerr, Sulphurets, and Mitchell zones, have much stronger and pervasive phyllic alteration, with a lower copper to gold ratio, and a geochemical signature that suggests positioning consistent with a shallow setting in a copper-gold porphyry hydrothermal system. The altered areas are often intensely foliated and deformed, leading and previous workers to suggest that regional compressive deformation was focused in these less competent rocks and pre-existing structures.

A large hydrothermal alteration system is associated with the earlier intrusions. It covers an area of over 35 square kilometers and is dominated by pyrite rich phyllic-argillic assemblages, resulting in intense gossanous exposures in uncovered and eroded areas. This extensive alteration and mineralization system developed as a result of hydrothermal activity focused on hypabyssal, Late Jurassic “Mitchell” intermediate, porphyritic intrusions. The model is best described as a gold-enriched copper porphyry system controlled by a series of dikes, sills and plugs rather than a single stock. Mineralization occurs typically associated with quartz veinlet stockworks and sheeted veinlet arrays mainly in altered host rocks adjacent to the intrusions. Less commonly, mineralized intrusive-hydrothermal breccias cut through previously veined and mineralized rocks.

Drilling and surface rock chip sample confirms the alteration and mineralization is continuous over distances of hundreds of meters. Post mineralization deformation has modified original geometries and remobilized metals, contributing to the homogeneity and “smoothness” of copper and gold mineralization, especially at the Mitchell zone. Principal sulfides are pyrite and chalcopyrite, with minor molybdenite, and trace amounts of tennantite, bornite, sphalerite, and galena. All mineralization is hypogene, except for a small remnant of preserved supergene mineralization at the south end of the Kerr zone which hosts some chalcocite enrichment, at the Main Copper occurrence where a remnant

of leached capping with minor native copper and oxide mineralization is preserved at the highest elevations, and intervals of partially leached and oxidized sulfides in weathered rocks near the surface. Leaching of mineralization in frost shattered rocks at higher elevations, with precipitation at lower elevations where groundwaters surface near the valley floors is an ongoing process. Figure 7-1 is a geologic map of the greater Mitchell Creek area that shows surface geology, structures, drill hole traces along with quartz and pyrite contours.

Mitchell Zone Geology

Lithology

The Mitchell zone is exposed in Mitchell Creek valley through an erosional window exposing the footwall of the Mitchell Thrust Fault. The zone is a moderately dipping, roughly tabular gold-copper deposit measuring approximately 1,600 meters along strike, 400 to 900 meters down dip, and at least 300 to 600 meters thick. It consists of a foliated, schistose zone of intensely altered and sulfide bearing rocks, with a variably distributed stockwork of deformed and flattened quartz veinlets. The schistosity generally follows an east-southeast direction, and dips steeply to moderately to the north. The Mitchell zone is considered to lie within the spectrum of the gold-enriched copper porphyry environment.

Metals, chiefly gold and copper (in terms of economic value), are generally at low concentrations, finely disseminated, stockwork or sheeted veinlet controlled, and pervasively dispersed over dimensions of hundreds of meters. Grades diminish slowly over large distances; sub-economic grades are encountered at distances of several hundreds of meters beyond the interpreted centre of the system. This is distinct from the Sulphurets and Kerr zones, where there are more abrupt breaks in grade due to higher structural complexity and juxtaposition of weak and moderate grade domains by faulting, both syn-mineral structures controlling breccia contacts, and post-mineral faulting and displacements.

Due to the intensity of hydrothermal alteration and strong post-mineral shearing, especially at Mitchell Creek, it is difficult to impossible to recognize the original protolith. This is typical of phyllic-argillic or quartz-sericite (illite)-pyrite altered rocks. In chlorite-sericite and propylitic altered rocks, a homogeneous, tuffaceous texture is often observed, and the host is believed to be intermediate volcanic tuffs or volcaniclastics. However, these textures may in part be shear related. Diffuse, ghost porphyritic textures may reflect dikes of the Mitchell intrusions. Rare, meter-scale, aphanitic intermediate dykes are post-alteration and unmineralized.

Below the Mitchell thrust fault in the drilled area, alteration intensity gradually diminishes westward. Where not obliterated by alteration, fine to coarse, lithic to cystal, tuffaceous, intermediate volcanics are dominant, followed by vaguely bedded, fine

grained volcaniclastics and argillites, more common to the west. Government mappers have assigned the stratigraphy under the Mitchell fault to the Jurassic Hazelton Group, however in many ways it more closely resembles descriptions of the Triassic Stuhini Group. Within the central and eastern portions of the drilled area, intervals of bleached, vaguely coarse porphyritic textured rocks may be altered dikes of the Mitchell intrusive suite.

Above the Mitchell fault, alteration is mainly confined to siliceous hornfelsed zones adjacent to porphyritic monzonite and granitic Mitchell intrusions. The host rocks are mostly dark, fine grained volcaniclastics and argillites assigned to the Triassic Stuhini Group. The intrusions appear to have thick, sill-like geometries, with thin, anastomizing dykes in the contact zones. Similar intrusives and surrounding siliceous alteration zones have been mapped above the Mitchell Thrust Fault on both sides of Mitchell Creek Valley.

Alteration

The general pattern is intense phyllic-argillic (quartz-sericite (illite)-pyrite) alteration at the east side of the drilled area, which gradually diminishes to the west. This is characterized by complete loss of mafics, introduction of mm to cm scale, deformed quartz veinlets in stockwork and sheeted arrays, with mostly creamy white to grey sericite and/or illite as the interstitial vein component. There are clearly multiple stages of quartz veining. Later veins are rich with coarse pyrite, often with molybenite, and cm scale, near massive coarse pyrite veins are common. The phyllic alteration has a strong foliation best manifested in sericite rich intervals. Sheeted quartz veinlets often follow the foliation, and may indicate deformation of pre-existing veins, or perhaps contemporaneous formation of quartz veinlets and deformation. In some surface exposures, intensely deformed zones contain coarse clasts of rotated, previously veined material, and strong shear textures are noted in microscopic thin sections.

The highest concentrations of pyrite and quartz veinlets are generally strongly coincident with phyllic-argillic alteration. The concentration diminishes gradually westward, however there are wide intersections at depth of intensely veined to near massive veins and breccias of hydrothermal quartz. These have a strong magnetite and potassic feldspar component and the highest continuous Au-Cu grades, suggesting hotter and deeper mineralizing conditions.

Later veins cut through the clasts and sericite rich matrix. There are also post-deformational, coarse, blotchy and random quartz-calcite-chlorite decimeter scale veins as well as mm scale, random, metamorphic calcite veinlets. Coarse chalcopyrite is often observed in the late calcite veinlets and likely has been remobilized.
The west side of the drilled area is dominated by propylitic alteration, characterized by pervasive chloritization of mafics, and quartz-pyrite alteration of most other silicates. This alteration is also stockwork veinlet controlled. The degree of foliation is much less than the phyllic zone to the east. The abundance of epidote and calcite increase westward.

Some phyllic alteration is present, but is restricted in extent and is probably structurally confined.

There is a widespread transitional alteration facies of pale green sericite and/or bleached chlorite which may reflect partial or diminishing phyllic-argillic alteration of preexisting propylitic and local potassic alteration. The highest gold and copper grades are roughly coincident with this transitional area.

There are apparent correlations between the logged alteration units, element distributions, quartz vein frequency and volume, and pyrite concentrations which partly verify the logging and help to explain the distribution of gold and copper. These include:

Ca, Mg – low concentrations of these elements are closely correlated to intense phyllic alteration and reflects strong depletion.

Na – an area of low concentration is closely coincident with the transition from strong phyllic in the east and propylitic in the west. This inversely follows the overall gold and copper distribution and suggests sodium depletion thus higher fluid temperatures.

Pyrite and Quartz Veinlets – The highest concentrations of pyrite, quartz veinlets and frequency of quartz veinlets (based on visual estimates) are strongly coincident with phyllic alteration. The concentration of these items gradually diminishes westward.

Mineralization

Gold and copper mineralization is low-grade and dispersed over a very large area, and is related to very fine grained disseminated chalcopyrite. Drilling has defined a central or core area with grades greater than 0.8 g/t Au and 0.2% Cu. From this core area, grades diminish very gradually to the north, east, and west in surface plan. The higher grade core appears to trend moderately northwards, which is at right angles to the current drill hole grid orientation. Mineralization remains open down dip to the north.

Within the higher grade core area, gold and copper grades correlate closely with one another. The Cu /Au ratio tends to be slightly higher closer to the phyllic-propylitic transitional area. In low-grade peripheral areas, the Cu /Au grades tend to be the highest. The gold and copper distribution is remarkably smooth and continuous with grades decreasing very gradually outwards from the higher grade core. There are very few sharp grade contacts. These observations suggest that the deposit was the generated by a large, stable hydrothermal system with a low thermal gradient within homogeneous host rocks. The distribution was minimally disrupted by late faulting with only minor offsets.

A few key observations are noted below for some key trace metals:

Ag – Silver shows a close correlation with gold, however the concentration is low, averaging only about 3 to 4 g/t in the mineralized central core area.

As – Arsenic, is generally inversely proportional to the distribution of gold. Within the central mineralized area, grades average approximately 0.003%. This distinguishes Mitchell Creek from other gold enriched porphyry deposits which are commonly elevated in arsenic due to overprinting high-sulphidation hydrothermal fluids.

Mo – Molybdenum is distinctly low in concentration and inversely proportional to the gold and copper distribution. It averages about 50 ppm within the central area, but increases to over 100 ppm in intervals around the periphery of the core mineralized area.

Pb, Zn – These are also low in concentration, and inversely proportional to the gold and copper distribution. The pattern of Pb, Zn and Mo distribution is characteristic of large porphyry deposits.

Structure

In strongly altered rocks beneath the Sulphurets and Mitchell thrust faults, intense alteration and foliation typically prevent recognition of stratigraphic orientations. Regional mapping by Provincial geologists indicate Jurassic Hazelton Group rocks exhibit overturned folds that are southeast vergent in the region of Kerr-Sulphurets. The thrusts are also southeast vergent. Triassic Stuhini Group rocks above the faults form the east side of a broad north plunging anticlinorium.

Due to mineralogical differences, the phyllic altered rocks were thought to be more susceptible to metamorphism resulting from regional deformation. This is evident at Kerr-Sulphurets, Mitchell Creek, and Iron Cap, where foliation is most intensely developed in hydrothermally altered phyllic zones. The orientation of the foliation tends to roughly parallel the trace of the Sulphurets thrust fault. At Kerr, it dips to the west; at Sulphurets to the northwest; at Mitchell Creek to the north-northeast; and at Iron Cap to the northwest.

Post-mineralization deformation resulting in re-mobilization of metals during the Cretaceous has probably contributed to the homogeneity of grades.

2007 DRILLING CAMPAIGN

Seabridge Gold completed a helicopter supported diamond drilling program at Mitchell Creek in 2007. Thirty-seven holes were drilled by four different contractors for a total of 15,293.52 meters. Radius Drilling Corporation from Prince George, B.C. drilled 21 holes totaling about 8,081 meters or about 53% of the 2007 drilling campaign using one of their Radius 2000 hydraulic drill rigs primarily with NQ2 drilling tools. Driftwood Diamond Drilling Ltd. from Smithers B.C. drilled 8 holes totaling about 3,045 meters or about 20% of the total 2007 drilling campaign using a Hydracore 2000 drill primarily with NQ2 tools. Blackhawk Drilling from Smithers, B.C. drilled 6 holes totaling about 2,777 meters or about 18% of the 2007 campaign using primarily NQ drilling tools. Hy-Tech Drilling Ltd. from Smithers, B.C. drilled 2 holes totaling about 1,390 meters or about 9% of the total 2007 campaign using a Tech-5000 Fly drill using NQ rods.

All drilling was helicopter supported using an Eurocopter A-Star model 350B2 that was contracted from Lakelse Air Ltd. from Terrace B.C. The drilling operations were conducted from the Sulphurets Creek camp which is located southwest of the Mitchell zone.

Accommodation for all contract and permanent staff was provided by a tent camp operated by Seabridge established at the same site as the 1992 camp, which is located about 1 kilometer west of Sulphurets Lake. Due diligence of helicopter equipment, flight personnel and fuel management was contracted to Matrix Helicopter Solutions of Kelowna, B.C.

First aid, cooking, camp construction, maintenance and drill pad construction staff were supplied by CJL Enterprises from Smithers B.C. Expediting was carried out by Granmac Services out of Stewart B.C. Core splitters were obtained from Tahltan Native Development Corporation, Dease Lake, B.C. All camp facilities supervision, technical program supervision, and core logging were carried out by employees of Seabridge Gold Inc.

Collar Locations

Drill holes were collared on roughly 100 to 200-meter spaced centers depending on local topographic constraints and oriented perpendicular to the local trend of foliation and dominant sheeted vein or deformed quartz stockwork array. The drill hole collars were initially located using handheld GPS instruments. Completed drill holes were surveyed by differential GPS methods by employees of Seabridge. Additionally, selected co-ordinates were surveyed by All North Surveying for quality control. The drill hole collar coordinates for the historical drill hole database are in UTM coordinates using NAD 27 ZONE 9 for Canada.

Table 4: 2007 Drill Hole Data

Hole ID	Azi-muth	Dip	Easting	Northing	Elev.	Depth	Contractor	Start Date	End Date	Logger	Core Diameter
M-07-24	190	-70	423218	6265494	840	597.25	Radius	5-Jul-2007	12-Jul-2007	MS, TD	NQ2/BQ
M-07-25	188.4	-66	423007	6265416	821	478.6	Blackhawk	28-Jun-2007	5-Jul-2007	MS	NQ
M-07-26	190	-55	423304	6265376	851	472.72	Blackhawk	12-Jul-2007	21-Jul-2007	MS, TD	NQ
M-07-27	190	-55	423308	6264811	1155	356	Radius	15-Jul-2007	20-Jul-2007	PE	NQ2
M-07-28	190	-55	423536	6264960	1089	398.37	Radius	21-Jul-2007	26-Jul-2007	PE	NQ2
M-07-29	190	-55	422942	6265020	922	336.48	Blackhawk	22-Jul-2007	27-Jul-2007	TD	NQ
M-07-30	190	-55	423508	6264784	1191	194.46	Radius	27-Jul-2007	29-Jul-2007	PE	NQ2
M-07-31	190	-55	423101	6264793	1081	233.16	Blackhawk	27-Jul-2007	01-Aug-07	MS	NQ
M-07-32	190	-55	423276	6264638	1234	364.54	Radius	30-Jul-2007	4-Aug-2007	PE	NQ2
M-07-33	190	-65	422845	6264185	1020	574.22	Blackhawk	2-Aug-2007	12-Aug-07	MS	NQ
M-07-34	190	-70	423147	6264889	1050	486.44	Radius	6-Aug-2007	16-Aug-2007	TD	NQ/BQ
M-07-35	195	-80	422857	6265464	880	682.14	Driftwood	14-Aug-2007	15-Sep-07	MS, TD	NQ
M-07-36	190	-55	422920	6264794	1031	77.11	Radius	16-Aug-2007	18-Aug-2007	TD	NQ2
M-07-37	190	-60	423622	6265388	897	428.24	Radius	18-Aug-2007	23-Aug-2007	TD, PE	NQ2
M-07-38	195	-90	422744	6264730	1020	300.21	Driftwood	24-Aug-2007	27-Aug-2007	PE	NQ
M-07-39	190	-90	422930	6264691	1081	285.89	Radius	24-Aug-2007	29-Aug-2007	TD	NQ2
M-07-40	195	-50	422744	6264730	1020	251.14	Driftwood	27-Aug-2007	30-Aug-2007	PE	NQ
M-07-41	190	-50	422930	6264692	1080	197.81	Radius	29-Aug-2007	01-Sep-07	MS	NQ
M-07-42	190	-60	422079	6264933	929	355.68	Driftwood	31-Aug-2007	6-Sep-2007	PE	NQ
M-07-43	190	-55	423706	6264943	1086	312.71	Radius	01-Sep-07	05-Sep-07	MS	NQ
M-07-44	190	-63	423665	6265706	935	646.14	Radius	5-Sep-2007	14-Sep-2007	PE	NQ2
M-07-45	190	-75	423335	6265545	860	650.72	Radius	15-Sep-2007	25-Sep-2007	MS, TD	NQ/BQ
M-07-46	190	-55	422728	6264981	856	424.3	Driftwood	16-Sep-2007	23-Sep-2007	TD	NQ
M-07-47	190	-75	423124	6265510	865	442.55	Driftwood	28-Sep-2007	4-Oct-2007	PE	NQ
M-07-48	190	-55	423272	6265078	967	394.39	Radius	26-Sep-2007	2-Oct-2007	TD	NQ2
M-07-49	10	-70	423226	6265172	919	396.85	Radius	2-Oct-2007	7-Oct-2007	PE	NQ2
M-07-50	195	-60	423567	6265107	973	342.9	Radius	3-Oct-2007	7-Oct-2007	MS	NQ
M-07-51	190	-55	423051	6265035	897	431.57	Driftwood	5-Oct-2007	10-Oct-2007	PE	NQ
M-07-52	190	-55	423439	6265089	1010	378.87	Driftwood	7-Oct-2007	14-Oct-2007	MS	NQ2
M-07-53	190	-70	422689	6265360	820	674.79	Radius	8-Oct-2007	22-Oct-2007	MS	NQ2/BQ
M-07-54	190	-75	422903	6265348	830	670.45	Hy-tech	9-Oct-2007	18-Oct-2007	PE	NQ
M-07-55	190	-65	422845	6265125	800	414.2	Driftwood	11-Oct-2007	16-Oct-2007	TD	NQ
M-07-56	190	-60	423488	6265267	905	428.25	Radius	14-Oct-2007	19-Oct-2007	MS	NQ2
M-07-57	190	-65	422660	6265150	780	425.18	Driftwood	17-Oct-2007	22-Oct-2007	TD	NQ
M-07-58	190	-85	423007	6265420	821	720	Hy-tech	19-Oct-2007	27-Oct-2007	PE	NQ
M-07-59	190	-55	423065	6265182	830	437.39	Radius	22-Oct-2007	27-Oct-2007	MS	NQ2/BQ
M-07-60	190	-65	422493	6265303	808	388.6	Radius	22-Oct-2007	29-Oct-2007	TD, MS	NQ2

Drilling Conditions

Drilling conditions were generally very good. Overburden was not excessive and rock quality was typically very high except in isolated fractured or sheared zones where the rock easily broke along foliation planes. Overall average RQD was about 74 percent and core recovery averaged about 95%. The frequency of natural breaks averaged about 9.6 per meter. Poorer recoveries were obtained in fractured and sheared zones especially in

brittle, siliceous hornfelsed rocks at shallow depths primarily in the periphery of the mineralized zone.

Drill Core Processing

Drill core was placed into wooden trays directly upon emptying the core tube at the drill site. A wooden run block was marked with the hole depth in meters was placed in the core trays upon the completion of each drill run, which in good conditions was based on full core runs of three meters. Core tubes and rods were in metric lengths. The core boxes were covered with a plywood lid which was securely nailed to the core box and then placed in a metal basket for helicopter slinging. The baskets were slung by helicopter to camp, typically after the morning shift change, depending on productivity and weather conditions.

At camp, the core basket was placed near the core logging shack. Each box was layed out in sequence on elevated racks in the core shed. The core was examined for condition, missing core, and depth tag errors. Boxes were labeled with black felt tip pens and embossed steel tags containing the hole number, depth, and box number. The core was then washed with fresh water. Geotechnical data including recovery, RQD, and natural breaks were recorded for each drill run, as marked by the wooden core run blocks. This information was recorded by the geologist or trained logging assistant under direct supervision of a geologist.

The geologist then recorded key geologic information including lithology, alteration, structure, and mineralization using a pre-determined format and coding system. The data were either entered directly into the digital database or onto paper logs which was then entered into the digital database at the camp office. The geologist or assistant under the direct supervision of the geologist marked sample intervals on the core at fixed 2-meter-long intervals or at geological contacts so that each sample was 2 meters or less which is in line with accepted industry practices for this style of mineralization.

The core at the beginning of each sample was marked with a wax pencil and a Teflon coated paper tag with a unique identification number, which was stapled to the core box adjacent to the wax marking. Duplicates of the paper tag with the identification number were also placed at the beginning of each sample and were placed on the sample bag that was sent to the assay lab. Another duplicate of the tag, with the identification number, hole number and depth interval was stored. This information was entered into the digital database assay table. The entire hole (excluding any recovered overburden) was sampled. The core was then digitally photographed. All digital photo files are maintained in the company's digital database. A wax pencil was then used to mark a cut line along the top of the drill core to avoid any sampler induced selection bias and to ensure that the same side of the halved core relative to its placement in the box was put into the sample bag that was sent for assay.

The 2007 drill core was sawn into primarily 2-meter-long samples, which were then shipped off site where they were assayed for gold, copper, and other metals. Of the 7,686 samples that were collected, 7 percent were less than 2-meters-long, 90% were exactly 2-meters-long and 3% were longer than 2-meters. In 2007, approximately 99% of drilled meterage was assayed. The 37 holes that were drilled in 2007 averaged about 413 meters in length. Drill hole M07-24E extended a 2006 hole (M-06-24) from a depth of about 356 meters to nearly 600 meters. After completing the 2007 drilling campaign, the Mitchell zone has been drilled to roughly 125-meter centers. The "core" portion of the deposit has been closed down to roughly 100-meter centers over an area, which measures approximately 1,400 meters (east-west) by 500 meters (north-south).

Sample Preparation and Dispatch

Upon completion of logging and sample demarcation, the core boxes were moved to the core cutting facilities in camp, usually the following day. The core cutting building is a 14'x16' plywood platform, covered with a poly tarp on aluminum poles. The walls were left open to facilitate air circulation and prevent dust contamination. Three gasoline engine powered saws with 12" diamond toothed blades designed for rock cutting were utilized on day shifts only. The saws were mounted on secure wooden stands at waist height. The saw blades were cooled, cleaned, and lubricated with fresh, non-recirculated water during cutting. The saw operator placed uncut core boxes on tables adjacent to the saws, and cut each piece of core sequentially within each marked sample interval. The assay half of the sample was placed in a heavy duty polythene bag and the other half was returned to the core box. Once a sample interval was completely sawn, the corresponding sample tag number was stapled to the inside at the top of the bag, and the bag was secured with staples. The sample number was also written on the bag with a permanent felt tip marker.

The bags were placed sequentially in rows on pallets or on the floor. Upon completion of a batch of 33 (see below), the samples were placed into large polyweave (rice) shipping bags, six per bag. The polyweave bag was labeled with the project number, sample numbers, shipment number, and lab address, and then secured with plastic tie straps. In addition, for security purposes the polyweave bag was also secured with a uniquely numbered tie strap, and the number recorded on the retained copy of the sample transmittal form. The other copy of the sample transmittal form was placed in the last shipping bag of each batch. The bags were stored adjacent to the core cutting building or helicopter pad until a complete shipment was ready, which usually included several batches. During normal production and good weather, shipments were sent out at least every two days.

The sample shipment was placed inside the project chartered helicopter or on rare occasions, put inside a cargo net slung below the helicopter and flown directly to the Granduc Road staging area and unloaded. At the staging area the shipment was either stored and locked inside a metal bulk shipping container until a truck contracted from

Granmac Services arrived from Stewart or transferred directly to a waiting truck. The truck was driven to Stewart where the samples were unloaded at the sample preparation facilities by Eco Tech Laboratories personnel. Occasionally the samples were taken directly to Stewart via helicopter and transferred to the prep lab by truck contracted by Granmac. The prep lab took an inventory of the shipment and confirmed that the numbered tie strap was not been broken or tampered with. Eco Tech then sent notification of the receipt of shipment with tie strap and sample numbers to Seabridge personnel at camp who confirmed the sample shipment.

Analytical Procedures

At the facilities in Stewart, samples were sorted and dried (if necessary). The samples were crushed through a jaw crusher and cone or roll crusher to –10 mesh. The sample was split through a Jones riffle until a –250 gram sub sample was achieved. The sub sample was pulverized in a ring and puck pulverizer so that 95% of the material passed a -140 mesh screen. The sample was then rolled to homogenize it. The resulting pulp sample was then placed in a numbered paper envelope and securely packed in cardboard boxes. These boxes were shipped via Greyhound freight services to the Eco Tech Laboratory facilities located in Kamloops, B.C.

Approximately 7,686 diamond core samples were collected from the 2007 drilling program and analyzed by Eco Tech Lab out of Kamloops, B.C. for gold, copper and a suite of other elements.

At the Eco Tech's lab in Kamloops, a 30 gram sample size was split out from the pulp envelope and then fire assayed using appropriate fluxes. The resultant doré bead was parted and then digested with aqua regia followed by an atomic absorption (AA) finish using a Perkin Elmer AA instrument. The lower limit of detection for gold is 0.03 g/t or 0.001 oz/t. For other metals, a multi-element ICP analysis was completed. For this procedure, a 0.5 gram sample was digested with 3 ml of a 3:1:2 (HCl: HN03:H20) which contains beryllium, which acts as an internal standard for 90 minutes in a water bath at 95°C. The sample was then diluted with 10 ml of water and analyzed on a Jarrell Ash CP unit. Eco Tech's ICP detection limits (lower and upper) are summarized in Table 13-1.

Quality Control Measures

Seabridge essentially implemented the same quality control procedures that they used for their 2006 Mitchell program. Different standard reference material (SRM) sources were used in 2007 versus 2006. They included blank material obtained from landscaping materials (granite and marble) along with different commercially certified standards. Assay quality control measures included the insertion of a sample blank and pulp standard within each laboratory batch of approximately 35 samples. Thus a complete batch contained a minimum of one blank and one pulp standard, with the remainder being core samples. The blank and pulp standard were numbered using the same number

sequence that was used for the core samples and inserted into each batch shipment at the completion of sawing the core samples for a given batch.

The majority of the pulp standards that were used by Seabridge for their 2007 drilling/sampling campaign were purchased from CDN Resource Laboratories Ltd. (CDN) out of Delta, B.C. Three CDN standards (CDN-GS-12, CDN-GS-13, and CDN-CM-1) were prepared from material that was collected from the Casino copper-gold-molybdenum porphyry property that is located in northern British Columbia. These standards have certified gold and copper values that are definitely relative to the type and tenor of mineralization that has been identified at the Mitchell zone. In the author's opinion, these standards are appropriate and reasonable. About 40 of the Analytical Solutions Ltd. five standards that were remaining from their 2006 drilling campaign.

In addition to the insertion of control samples with each batch, Seabridge also submitted duplicate core samples by sawing one half of the drill core into two ¼ core splits that were submitted as individual samples to Eco Tech. Approximately 2% of the total samples submitted to Eco Tech in 2007 were duplicate core samples. About 10% of the 2007 samples (760 samples) that were assayed by Eco Tech were re-assayed as same pulp "cross-checks" by ALS Chemex of North Vancouver, B.C.

For gold, both Eco Tech and Chemex employed the same assay preparation and measurement technique. For other metals, the cross-checks compared Eco Tech ICP analyses with ALS ore grade, AAS finish analyses. Both methods utilized a triple acid digestion. For finely disseminated, low grade base metal mineralization similar to that which occurs at the Mitchell zone, the ICP analyses are generally considered to be as reliable, or more reliable, than ore grade, AAS finish analyses.

STATEMENT OF COSTS

	$ CDN
Field Personnel (1,130 person-days @ $390/day)	439,000
Consultants (Mapping, Surveying)	25,500
Food and Accomodation	71,500
Mobilization/Demobilization	17,600
Aircraft Support	1,612,100
Vehicle Rentals	9,900
Equipment and Supplies (incl. expediting and freight)	371,900
Instrument Rentals	11,600
Laboratory Analysis	209,100
Contract Jobs (15,293.5m core drilling @ $130.51/m)	1,996,000
TOTAL	$ 4,764,900

Exploration Work type	Comment				Totals
Personnel (Name) / Position	**Field Days (list actual days)**	**Days**	**Rate**	**Subtotal**	
Michael Savell / Geological contractor	June 19 - Nov. 6	114	$268.79	$30,641.64	
CJL Enterprises Ltd. / cooks, first aid att., pad builders	June 20 - Nov. 3	625	$412.69	$257,933.81	
Tahltan Northern Exploration Services Ltd. / core cutters	June 26 - Nov. 3	380	$382.18	$145,228.40	
Tsetsaut Consultation Society / labourers	Oct. 8 - Nov. 3	24	$250.00	$6,000.00	
				$439,803.85	**$439,803.85**
Geochemical Surveying	**Number of Samples**	**No.**	**Rate**	**Subtotal**	
Drill (cuttings, core, etc.)	8290 core and quality control samples	8290	$25.22	$209,101.82	
				$209,101.82	**$209,101.82**
Drilling	**No. of Holes, Size of Core and Metres**	**No.**	**Rate**	**Subtotal**	
Diamond	37 holes, NQ to BQ diameter, 15,294.5 metres	15295	$130.51	$1,996,030.13	
				$1,996,030.13	**$1,996,030.13**
Other Operations		**No.**	**Rate**	**Subtotal**	
Eagle Mapping	topographic surveying	1	$10,101.30	$10,101.30	
Allnorth Consultants	topographic surveying	1	$15,379.33	$15,379.33	
				$25,480.63	**$25,480.63**
Transportation		**No.**	**Rate**	**Subtotal**	
Airfare	trips	10	$1,760.00	$17,600.00	
truck rental	months	5	$1,980.00	$9,900.00	
Helicopter (hours)	hours	848	$1,659.96	$1,407,563.08	
Fuel (litres/hour)	hours	848	$241.15	$204,487.97	
				$1,639,551.05	**$1,639,551.05**
Accommodation & Food		**No.**	**Rate**	**Subtotal**	
Hotel	nights	50	$79.57	$3,978.52	
Camp equipment and construction materials	total camp person days	3170	$18.76	$59,464.79	
Meals	total camp person days	3170	$21.29	$67,474.88	
				$130,918.19	**$130,918.19**
Miscellaneous					
Telecommunications				$31,843.19	
Expediting				$3,330.45	
Core boxes				$37,386.65	
Diamond saw blades				$28,960.10	
Drill and Camp fuel				$192,520.15	
Freight				$17,812.06	
Miscellaneous				$549.86	
				$312,402.46	**$312,402.46**
Equipment Rentals		**No.**	**Rate**	**Subtotal**	
Reflex Instrument	Downhole survey tool months	5	$1,639.65	$8,198.27	
Instrumentation GDD	Magnetic Susceptibility Meter months	5	$682.82	$3,414.09	
				$11,612.36	**$11,612.36**
TOTAL Expenditures					**$4,764,900.50**

STATEMENT OF QUALIFICATIONS

I, Michael John Savell declare that,


- I am a geologist and have been continuously employed in this field since May, 1980. My address is 1004 Roxborough Drive, Oakville, Ontario, Canada, L6M 1E3.

- I graduated from Dalhousie University in Halifax, Nova Scotia with a B. Sc. (Honours) Degree in geology in 1980.

- I am a Practicing Member of the Association of Professional Geoscientists of Ontario (#0477) and the Association of Professional Engineers and Geoscientists of British Columbia (#20842)

- I undertook contract geological work from Seabridge Gold Inc. on the Kerr-Sulphurets-Mitchell Project in 2007, and was on site for most of the duration of the drilling program, from June 19th to November 6th.

Dated at Toronto, Ontario on May 15th, 2008



Michael Savell
President, MJS Geological Services Inc.

Bibliography and References

Alldrick, D.J., and Britton, J.M., 1991, Sulphurets Area Geology, Openfile 1991-21 Geology Maps, British Columbia Geological Surveys Branch.

Carson, D. 2003: Mineralogy and Interpretation of Mineralized an Hydrothermally Altered 2004 Field Samples from the Kerr-Sulphurets Porphyry Copper-Gold Property, British Columbia – Carson Geomin Report KS-01, Proprietary Report Commissioned by Noranda Inc.

Carson, D. 2004: Mineralogy and Interpretation of Mineralized an Hydrothermally Altered 2004 Field Samples from the Kerr-Sulphurets Porphyry Copper-Gold Property, British Columbia – Carson Geomin Report KS-02, Proprietary Report Commissioned by Noranda Inc.

Ditson, G.M., 1997, Kerr/Sulphurets Resource Estimates, Internal Placer Dome Canada Memorandum dated January 23, 1997.

Ditson, G.M., Wells, R.C., and Bridge, D.J., 1995, Kerr: The Geology and Evolution Of A Deformed Porphyry Copper-Gold Deposit, Northwestern British Columbia, in Porphyry Deposits of the Northwestern Cordillera of North America, Canadian Institute of Mining, Metallurgy and Petroleum, Special Volume 46, p. 509-523.

Fowler, B.P., and Wells, R.C., 1995, The Sulphurets Gold Zone, Northwestern British Columbia, in Porphyry Deposits of the Northwestern Cordillera of North America, Canadian Institute of Mining, Metallurgy and Petroleum, Special Volume 46, p. 484-498.

G & T Metallurgical Services, Ltd., 2007, Preliminary Assessment of Mitchell Zone Samples, Kerr-Sulphurets, British Columbia, Canada, report prepared for Seabridge Gold, 19 pages

Gray, M.D., and Munguia, J, 2006, Field Review Summary Report, Kerr-Sulphurets Project, Iskut River Region, British Columbia, Canada, Proprietary Report Commissioned by Seabridge Gold Inc.

Henderson, J.R., Kirkham, R.V., Henderson, M.N., Payne, J.G., Wright, T.O, and Wright, R.L., 1992. Stratigraphy and Structure of the Sulphurets Area, British Columbia, in Current Research, Part A: Geological Survey of Canada, Paper 92-1A, p. 323-332.

Kirkham, R.V., and Margolis, J., 1995, Overview Of The Sulphurets Area, Northwestern British Columbia, in Porphyry Deposits of the Northwestern Cordillera of North America, Canadian Institute of Mining, Metallurgy and Petroleum, Special Volume 46, p. 473-483.

Lechner, M.J., 2007, Mitchell Creek Technical Report, Northern British Columbia, NI 43-101 Technical Report prepared for Seabridge Gold, 104 pages
Lechner, M.J., 2008, Updated Mitchell Creek Technical Report, Northern British Columbia, NI 43-101 Technical Report prepared for Seabridge Gold, 98 pages

Lechner, M.J., 2008, Kerr-Sulphurets Technical Report, Northern British Columbia, NI 43-101 Technical Report prepared for Seabridge Gold, 119 pages

Lewis, P.D. Toma, A., Tosdal, R.M. (compilers), 2001, Metallogenesis of the Iskut River Area, Northwestern British Columbia, in Mineral Deposit Research Unit Special Publication Number 1.

Lewis, P.D., Thompson, J.F.H., Nadaraju, G., Anderson, R.G., and Johannson, G.G., 1993, Lower and Middle Jurassic Stratigraphy in the Treaty Glacier Area and the Geological Setting of the Treaty Glacier Alteration System, Northwestern British Columbia, In Current Research, Part A: Geological Survey of Canada Paper 93-1A, p. 75-86.

Margolis, Jacob, 1993, Geology and intrusion-related copper-gold mineralization, Sulphurets, British Columbia: unpublished PhD dissertation, University of Oregon, Eugene, 289 pages, 5 maps.

Margolis, J., and Britten, R.M., 1995, Porphyry-Style And Epithermal Copper-MolybdenumGold-Silver Mineralization In The Northern And Southeastern Sulphurets District, Northwestern British Columbia, in Porphyry Deposits of the Northwestern Cordillera of North America, Canadian Institute of Mining, Metallurgy and Petroleum, Special Volume 46, p. 499-508.


Martin, T. et al, 2004, Kerr-Sulphurets Project, Scoping Study – Tailings and Waste Rock Management, Proprietary Report by AMEC, Commissioned by Noranda Inc.


Savell, M., 2006, Diamond Drilling Report on the Mitchell Creek Area, Kerr-Sulphurets Property, Proprietary Report Commissioned by Xstrata Copper, 39 pages, 5 appendices

Savell, M., and Huard, A., 2005, Report On Diamond Drilling, Mineral Claims 516241, 516242, 516245, 516248, 516251, 516252 and 516253 Skeena Mining Division NTS 104B08, 104B09 56.52N, 130.25W owned by Seabridge Gold Inc., Work performed by Falconbridge Limited July 7 – September 4, 2005 (Assessment Report 28062)

Savell, M., and Huard, A., 2004, Report on the 2004 Exploration Program, Kerr-Sulphurets Property, For Noranda Inc./Falconbridge Ltd., Proprietary Report

Stantec Consulting Ltd., Environmental Evaluation of Kerr-Sulphurets Property, Northwestern B.C., 2003, Proprietary Report Commissioned by Noranda Inc.


KERR-SULPHURETS-MITCHELL PROJECT REGIONAL LOCATION
N
ISKUT RIVER
SNIP MINE
(closed)
ESKAY CREEK MINE
PARK
SKEENA RIVER
HIGHWAY 37
KERR-SULPHURETS-MITCHELL
PARK
UNUK RIVER
BOWSER LAKE
ice
WINTER TOTE ROAD
TONGASS NATIONAL FOREST AND
MISTY FJORDS NAT. MONUMENT
TUNNEL
GRANDUC MINE
(closed)
B.C.
ALASKA
HIGHWAY 37A
PREMIER MINE
(closed)
STEWART
0
30
kilometers


N
PROPERTY BOUNDARY
516,240
516,241
516,236
516,242
516,248
516,238
Mitchell Glacier
516,237
516,245
Mitchell Creek
MITCHELL ZONE
254,756
254,758
254,757
254,759
516,239
516,251
516,252
516,258
SULPHURETS ZONE
516676
516677
516375
516,254
516,259
516,255
516,256
516,253
516325
516328
516332
516330
Sulphurets Creek
516323
516,260
516333
516,269
516,262
516,261
KERR ZONE
516,267
Sulphurets Glacier
516,266
516,268
516,264
516,263
Drill Holes
MINERAL CLAIMS
PLACER CLAIMS
0
1
2
kilometres
KERR-SULPHURETS-MITCHELL
CLAIMS AND TENURE NUMBERS
FEBRUARY 2008
SEABRIDGE
GOLD INC.

420000 mE
422000 mE
424000 mE
426000 mE
6268000 mN
6266000 mN
6264000 mN
6262000 mN
6260000 mN

N

PROPERTY BOUNDARY

IRON CAP

NORTH MITCHELL

MITCHELL ZONE (Feb, 2008)
1,402 M t @ 0.17% Cu, 0.66 g/t Au
(5,119 M lb Cu, 29.6 M oz Au)

Mitchell Creek

SECTION 15

SNOWFIELD
(Silver Standard Res.)
64 M t @ 0.013% Mo,
1.46 g/t Au
(3.02 M oz Au)
Dec., 2006

MAIN COPPER

ICEFIELDS

SULPHURETS ZONE
108.3 M t @ 0.22% Cu, 0.71g/t Au
(535 M lb Cu, 2.47 M oz Au)

SECTION 29700N

glacier

CANYON

MACQUILLAN

Sulphurets Creek

Sulphurets Lake

CAMP

SECTION 10600N

KERR ZONE
257.7 M t @ 0.45% Cu, 0.24g/t Au
(2,543 M lb Cu, 2.00 M oz Au)

Jurassic
- Late Mafic Intrusions
- Phyllic-Argillic Altn
- Siliceous-Hornfels Altn
- Mitchell Intrusions
- Hazleton Gr. Seds/Volcs


Triassic
- Stuhini Gr. Seds/Volcs


- Drill Holes
- Faults
- Mineralized Zones


0 1 2
kilometers


KERR-SULPHURETS-MITCHELL PROPERTY COMPILATION
FEBRUARY 2008


SEABRIDGE GOLD INC.


LEGEND
Jurassic
Late Mafic Intrusions
Phyllic-Argillic Alt'n.
Propylitic-Siliceous-Hornfels Alt'n
Mitchell Intrusions
Hazleton Gr. Sedx/Volcx
Triassic
Skybird Gr. Sedx/Volcx
Drill Holes
Faults
Bedding
Foliation
Jointing
Outcrop Area
Contour Interval = 20 meters
Au Assays
surface trace
0.00 - 0.25
0.25 - 0.50
0.50 - 0.75
>0.75 g/t
% Quartz Veining
>10%, >30%, >40%
% Pyrite
>2.5%, >5.0%, >7.5%
LG Pit Limits
(2008 resource model)
Upper edge of steep bluff
Composite Assays
Au g/t, Cu %
meters
SECTION 06
SECTION 07
SECTION 08
SECTION 09
SECTION 10
SECTION 11
SECTION 12
SECTION 13
SECTION 14
SECTION 15
SECTION 16
SECTION 17
SECTION 18
SECTION 19
SECTION 20
SECTION 21
422400 mE
422800 mE
423200 mE
423600 mE
424000 mE
424400 mE
6266000 mN
6265600 mN
6265200 mN
6264800 mN
6264400 mN
1200m
1100m
1000m
900m
800m
200
meters
Mitchell Glacier
NOTE: CONTOUR LINES UNRELIABLE IN THIS AREA
PROPERTY BOUNDARY
MITCHELL FAULT
TRENCH
MITCHELL ZONE PLAN
GEOLOGY, DRILL HOLE LOCATIONS,
AND Au-Cu COMPOSITE ASSAYS
Scale - 1:2,500
Date - Feb. 2008
SEABRIDGE GOLD INC.


1200 mN
1000 mN
800 mN
600 mN
0.77g/t Au, 0.19% Cu / 217.5m
0.53g/t Au, 0.16% Cu / 138m
0.61g/t Au, 0.15% Cu / 108m
M-06-05
WM-05-01
M-06-02
198.0
202.5
207.5
0
100
200
meters
Geology
Jurassic
Qtz-Ser-Py Alteration
Ser-Chl-Py Alteration
Chl-Ser-Py Alteration
Potassic Alteration
Mitchell Intrusions
Hazleton Gr. Sedis/Volcs
Triassic
Stuhini Gr. Sedis/Volcs
late mafic dykes
Au Assays
0.0 - 0.2
0.2 - 0.4
0.4 - 0.6
0.6 - 0.8
0.8 - 1.0
> 1.0 g/t
% pyrite: 5 - 7.5, >7.5
% qtz veins: 10 - 60, >60
LG PIT MAX. LIMITS
SEABRIDGE GOLD INC.
MITCHELL ZONE - SECTION 07
View Looking West
Date: Feb. 2008


M-07-41
M-07-39
M-07-36
M-07-29
M-06-13
M-06-07
M-07-25
M-07-58
M-06-10
0.41g/t Au, 0.12% Cu / 41.3m
0.33g/t Au, 0.11% Cu / 52.1m
0.97g/t Au, 0.28% Cu / 297.6m
0.68g/t Au, 0.20% Cu / 131.3m
0.70g/t Au, 0.15% Cu / 122m
0.75g/t Au, 0.19% Cu / 325.8m
0.78g/t Au, 0.25% / 294.1m
0.83g/t Au, 0.26% Cu / 469.6m
0.72g/t Au, 0.27% Cu / 715.5m
197.8
77.1
285.9
336.5
309.0
158.0
478.8
729.0
1000 mN
900 mN
800 mN
700 mN
0
100
200
meters
LG PIT MAX. LIMITS
Geology
Au Assays
Qtz-Ser-Py Alteration
Ser-Chl-Py Alteration
Chl-Ser-Py Alteration
Potassic Alteration
Mitchell Intrusions
Hazleton Gr. Seds/Volcs
0.0 - 0.2
0.2 - 0.4
0.4 - 0.6
0.6 - 0.8
0.8 - 1.0
> 1.0 g/t
Tsitsutl
Stuhini Gr. Sedv/Volcs
late mafic dykes
% pyrite: 5 - 7.5, >7.5
% qtz veins: 10 - 60, >60
SEABRIDGE GOLD INC.
MITCHELL ZONE - SECTION 11
View Looking West
Date: Feb. 2008


M-07-32
M-07-27
0.23g/t Au, 0.11% Cu / 227m
M-06-17
0.75g/t Au, 0.27% Cu / 150m
581-095
M-06-03
M-06-14
M-06-02
0.73g/t Au, 0.18% Cu / 42.6m
0.92g/t Au, 0.26% Cu / 219m
0.83g/t Au, 0.16% Cu / 268m
0.88g/t Au, 0.17% Cu / 202m
0.81g/t Au, 0.17% Cu / 423m
LG PIT MAX. LIMITS
meters
Geology
Au Assays
Qtz-Ser-Py Alteration
Ser-Chl-Py Alteration
Chl-Ser-Py Alteration
Potassic Alteration
Mitchell Intrusions
Hazleton Gr. Sedis/Volcs
Stuhini Gr. Sedis/Volcs
% pyrite: 5 - 7.5, >7.5
% qtz veins: 10 - 60, >60
SEABRIDGE GOLD INC.
MITCHELL ZONE - SECTION 15
View Looking West
Date: Feb. 2008


1200 mN
1000 mN
800 mN
600 mN
M-07-49
0.51g/t Au, 0.12% Cu / 311.7m
M-06-04
0.84g/t Au, 0.06% Cu / 24m
312.7
303.0
LG PIT MAX. LIMITS
0
100
200
meters
Geology
Jurassic
Qtz-Ser-Py Alteration
Ser-Chl-Py Alteration
Chl-Ser-Py Alteration
Potassic Alteration
Mitchell Intrusions
Hazleton Gr. Sedis/Volcs
Triassic
Stuhini Gr. Sedis/Volcs
late mafic dykes
Au Assays
0.0 - 0.2
0.2 - 0.4
0.4 - 0.6
0.6 - 0.8
0.8 - 1.0
> 1.0 g/t
% pyrite: 5 - 7.5, >7.5
% qtz veins: 10 - 60, >60
SEABRIDGE GOLD INC.
MITCHELL ZONE - SECTION 19
View Looking West
Date: Feb. 2008

APPENDIX 1

DRILL HOLE LOGS

LITHOLOGY CODES

Lith Code	Lith Type
ANDS	Andesite
CCSD	Chert/chemical seds
DDRT	Diorite/mafic intrusive
FDYK	Felsic Dike
FLTZ	Fault Zone
GRAN	Granitic porphyry
IVOL	Intermediate Volcanics, Massive Flows/Tuffs
NREC	No recovery
OVBD	Overburden
PAND	Porhyritic Andesite Intrusive
PHBX	Hydrothermal Breccia
PPFP	Feldspar Porphyry Intrusions
PQMZ	Quartz Monzonite
PSBX	Siliceous Hydrothermal Breccia
QTVN	Quatz vein
SARG	Volcaniclastics/Argillites
SCHT	Schist, unknown protolith (intensely altered)
SEDS	Undifferentiated seds
SSLT	Siltstone
VAAT	Andesite Ash Tuff
VALT	Andesite Lapilli Tuff
VATF	Andesite Tuff
VAXT	Andesite Crystal Tuff
VU	Volcanic, unknown protolith (intensely altered)
VUAT	Unknown Ash Tuff
VULT	Unknown Lapilli Tuff
VUTF	Unknown Tuff
VUXT	Unknown Crystal Tuff

ALTERATION CODES

Alt_Code	Alt_Code_Description
CARB	Carbonate veining, fault related
CL	Chlorite alteration
CL2	Chlorite alteration with Mag and Carbonate, no epidote
FEOX	Fe-Oxides due to weathering
HEM	Hematization of intrusives
IARG	Intermediate Argillic - green Ser, Chl, Py
KP	Potassic - K-Fd,Qt,Py,Cp (Porphyry)
PKBX	Potassic - K-Fd,Qt,Ser,Py,Cp (Hydrothermal Breccia)
PR	Propylitic - Chl,Ep,Py,Carb,Mag
PSBX	Silica Flooding - Qt,Ser,Py,Tour,Py (carb) (Hydrothermal Brx)
QA	Albitic (core area) - Ab,Cb,Chl,Py,Cp,Ser (Porphyry)
QB	Potassic - Bio,Qt,Py,Cp (Chl,Ser,Mo) (Porphyry)
QSP	Phyllic - Qt,Ser,Tour,Py, remnant Ks,Cp,Mo (Hydro. Brx+porph.)
QSPSTW	Phyllic - Qt,Ser,Py (>60% qtz veinlets)
QTVN	Late Quartz Veins
SI	Silica Flooding - Qt,Py,Cp (Tour,Ser) (Porphyry)
SIH	Silicification due to Hornfelsing - Qt, Py
SIL	Pervasive silicification

Alt Intensity	Alt Int Description
6	Intense
5	Strong
4	Moderate to Strong
3	Moderate
2	Weak to Moderate
1	Weak

Alt modifier	Descrip.
Bd	Banded
D	Disseminated
FF	Fracture Filling
Fr	Fracture Controlled
INT	Interstitial
MO	Mottled
P	Pervasive
Pch	Patchy
PD	Pods
Sp	Spotted
V	Vein

COLOR CODES

Code	Color:
W	White
G	Grey
N	Green
G N	Grey Green
N G	Green Grey
F	Off white
O	Orange
R	Red
T	Tan
B	Brown
P	Pink
K	Black
A	Pale
D	Dark
U	PURPLE
M	MAROON

TEXTURE CODES

Code	Texture
Ap	Aphanitic / Glassy
Bd	Banded
Ck	Crackled
Eq	Equigranular
Fo	Foliated
Ms	Massive
Mo	Mottled
Po	Porphyritic
Sk	Speckled
Sp	Spotted / Leopard like
Wm	Wormy

Intensity	Descrip.
5	Intense
4	Strong
3	Mod. to Strong
2	Moderate
1	Weak

STRUCTURE CODES

Code	Description
fl	Fault
fr	Fracture
jt	Joint
stk	Stockwork
stf	stockwork fr
stv	Stockwork v
stv	Stockwork v
stv	Stockwork v
stv	Stockwork v

OXIDATION CODES

Code	State:
1	fully oxidized
2	mostly oxidized w/ trace of sulfides
3	evenly mixed oxides and sulfides
4	mostly sulfides w/ some oxides
5	sulfides only

Code	Type
L	Limonite
H	Hematite
G	Goethite
J	Jarosite

Intensity	Descrip.
5	Intense
4	Strong
3	Mod. to Strong
2	Moderate
1	Weak

SEABRIDGE GOLD INC

KSM 2007 Drill Log

Hole ID: **M-07-24E**

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
356.8	409.6	Massive Quartz veining, with 5-20% remnant host material and pyrite (2-8%) and chalco from .3-.5% with local large clots.	G W, N	QTVN	Ck	2	IARG	P	6											5		
409.6	434.8	Intermdiate Volcanic, heavily altered with QSP plus minor chlorite mostly as replacement of lapilli. Qtz vns and qtz+py vns, tr moly. Qtz vns vary from 1mm to 20cm.	N G	IVOL			QSP	P	5					vn	10	70				5		
434.8	442.8	Alteration lessens, Mix QSP CL, CL slightly higher, Wormy qtz vns, some with pyrite vning.	G N	IVOL	Wm	2	QSP	P	4	CL	P	1		vn	18	70				5		
442.8	460.8	IARG less intense alteration overall	G N	IVOL	Wm	2	IARG	P	3	CL	P	1		vn	10	70				5		
460.8	526.8	Interm. Volc with vn swarms/stk work vns from .1cm to 30cm wide. w/ pyrite, chalco pyrite, cpy and chlorite (abn) also possible biotite. Several small faults 3-10cm.	D N G	IVOL			IARG	P	4	CL	Pch	1	45	stk	75		fl	0.1	40	5		
526.8	560.7	Increase in bleaching and Sericite, slight increase in sulfides(?) less chlorite, still stockworked, vns slightly thicker and crackled, more visible moly. Late stage qtz vns with chlorite inclusions/blebs.	N G, W	IVOL	Ck	2	QSP	P	4	CL	Pch	1								5		
560.7	597.3	IARG mod-stg, stockwork qtz vns, dis py plus py vnlets, cpy dis and micro vnlets, tr+ moly. Hole stopped due to slow penetration rate/depth.	G N	IVOL			IARG	P	3	QSP	Pch	3	42	stk	30	42				5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	9	Overburden/Casing		OVBD																		
9	16.1	Moderately schistose, propylitic altered, aphanitic to fine grained, many schistose, incompetent intervals. Weak to moderate qtz stwk veining, dominant set at 60d to CA. Rarely veinlets up to 10cm thick, with crackle and dissem py. Late qtz-Fe carb veinlets throughout.	GN	ANDS	Fo		IARG	P	4	QSP	Pch	3	53							5		
16.1	18		G	ANDS			QSP	P	4											5		
18	27		G	ANDS			IARG	P	4	QSP	Pch	3								5		
27	53.1	thicker qtz sulfide veins (>2cm) increase with depth from this point on	G	ANDS			QSP	P	4											5		
53.1	55.4		G	ANDS			IARG	P	4	QSP	Pch	3								5		
55.4	57		G	ANDS			QSP	P	4											5		
57	63.3	Andesitic volcanic with dark green-black, ragged lapilli and ash fragments aligned with foliation, highlighted in QSP altered intervals	N	VALT	Sk		IARG	P	4				55							5		
63.3	66.6	wormy py-cpy vein, 1-2cm, subparallel to CA.	G	VALT			QSP	P	4											5		
66.6	68.5	note alteration boundaries are diffuse, transitional	N	VALT	Sk		IARG	P	4											5		
68.5	70.8		N	VALT	Sk		QSP	P	5											5		
70.8	89		N	VALT	Sk		IARG	P	4											5		
89	90		N	VALT	Sk		QSP	P	2											5		
90	92.1		N	VALT	Sk		IARG	P	4											5		
92.1	96		N	VALT	Sk		QSP	P	4											5		
96	112		N	VALT	Sk		IARG	P	5											5		
112	116.3		N	VALT	Sk		QSP	P	5											5		
116.3	118.4		N	VALT	Sk		IARG	P	5											5		
118.4	120.7		N	VALT	Sk		QSP	P	5											5		
120.7	124.2		N	VALT	Sk		IARG	P	5											5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
124.2	125.7		N	VALT	Sk		QSP	P	5											5		
125.7	128		N	VALT	Sk		IARG	P	4											5		
128	131.7		N	VALT	Sk		QSP	P	5											5		
131.7	146.9		G	VALT			IARG	P	5											5		
146.9	148.7		G N	VALT			QSP	P	4													
148.7	153.1		G	VALT			IARG	P	4													
153.1	154		G N	VALT			QSP	P	4													
154	156		G	VALT			IARG	P	4													
156	157.5		G N	VALT			QSP	P	4													
157.5	159.2		G	VALT			IARG	P	4													
159.2	163	Variably phyllic altered, schistose, fine grained lapilli tuff, distinct grey-green, waxy textured lapilli aligned with schistosity. Veining preferentially follows schistosity, a few cross-cutting, also later wormy veins	G	VALT			QSP	P	4													
163	174.3		G	VALT			QSP	P	5													
174.3	175.5	Mafic dyke, fine grained, lacks schistosity, but mineralized - not one of the typical late, barren variety	N	DDRT			PR	P	1													
175.5	179.4	Strongly altered and veined volcanics as 159.2-173	G	VALT			QSP	P	5													
179.4	179.7	Mafic interval or weakly QSP altered remnant	N	VALT			QSP	P	2													
179.7	184.1		G	VALT			QSP	P	5													
184.1	184.4	Mafic interval	N	VALT			QSP	P	2													
184.4	185		G	VALT			QSP	P	5													
185	185.2	Mafic interval	N	VALT			QSP	P	2													
185.2	185.6		G	VALT			QSP	P	5													
185.6	185.8	Mafic interval	N	VALT			QSP	P	2													
185.8	189		G	VALT			QSP	P	5													
189	189.4	Mafic interval	N	VALT			QSP	P	2													
189.4	211.7		G	VALT			QSP	P	5													
211.7	212	Mafic interval	N	VALT			QSP	P	2													

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
212	226.4		G	VALT			QSP	P	5													
226.4	235	Mafic tuff, less altered equivalent of 159.2-173. Darker intervals have disseminated magnetite, a few chl-mt-carb veinlets	N	ANDS			PR	P	4													
235	249	variably QSP altered, veined, schistose, fine lapilli tuff, well mineralized.	G	VALT			QSP	P	5													
249	251.6	Patchy QSP alteration over older PR or IARG, sharp contacts at veins	G	VALT			QSP	P	3													
251.6	256.3		G	VALT			QSP	P	5													
256.3	261	as from 249-251.6	G	VALT			QSP	P	3													
261	265.4		G	VALT			QSP	P	5													
265.4	269.1	mixed QSP over PR alteration	G	VALT			QSP	P	3													
269.1	274.9	alteration and mineralization increasing with depth	G	VALT			QSP	P	5													
274.9	278.5	mostly massive quartz vein and silicified wall rock and encased fragments, late coarse py veins. Wall rock fragments have pale pink-brown hue, vague porphyritic texture - suggests intrusive hydrothermal breccia	G	QTVN			QSP STW	P	6													
278.5	280.5		G	VALT			QSP	P	5													
280.5	283	partial and patchy QSP alteration of dark chl-(biot)-py-mt alteration (hornfelsic)	G	VALT			QSP	P	3	CL	Pch	3										
283	291.2	heavily veined, wall rocks and enclosed fragments are mod. QSP altered.	G	VALT			QSP	P	5													
291.2	293.3	>60% crackled qtz veins and veinlets. QSP alteration decreases with depth	N G	QTVN			QSP STW	P	6													
293.3	297.5	as from 283-291.2	G	VALT			QSP	P	6													
297.5	304.5	75% crackled quartz veins and veinlets, QSP altered wall rocks and enclosed fragments, well mineralized. A few late pyrite veinlets.	G	QTVN			QSP STW	P	6													
304.5	308	as from 283-291.2	G	VALT			QSP	P	6													
308	309.9	distinct pink red-brown colored matrix, possibly potassic altered granite or hydrothermal breccia. Cp>py, increases with depth along with magnetite	G	VALT			KP	P	3													
309.9	313	50% crackled quartz veins and veinlets, dark altered wall rock fragments, probably very finely biotite-magnetite (potassic alteration)	G	QTVN			QSP STW	P	4													

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
313	316.4	75% quartz veins and irregular, deformed cm scale veinlets, mostly QSP altered wall rock fragments with abundant pyrite	G N	QTVN			QSP STW	P	6													
316.4	318.2	Dark green to black matrix, weakly magnetic, may be chloritized biotite alteration. Widely dispersed sulfides in veins and wall rocks. Bottom half is strongly schistose, lapilli texture visible. Thicker veins mostly at 45-60d to CA, mm and cm scale veinlets are irregular, deformed, wormy	K	VALT			KP	P	4				45									
318.2	320.5	unusual breccia texture due to fragmented, boudinaged, broken up quartz veins resulting from shearing. Foliated, lapilli texture. A few late, undeformed qtz veinlets.	K	VALT			KP	P	4													
320.5	323.8	Intense veining and deformation, variably QSP altered, a few patchy zones without QSP alteration are black to dark green probable preserved potassic alteration	G N	ANDS			KP	P	3	QSP	Pch	3										
323.8	325.2	Intensely veined, QSP altered, schistose zone	N	ANDS			QSP	P	5													
325.2	327.9	Potassic altered lapilli tuff, dark green to black chl-biot-mt-py, variably deformed qtz stockwork veining, weak and patchy QSP alteration. Py>cp A few late py veinlets.	K	VALT			KP	P	3													
327.9	328.9	Heavily veined, QSP altered, a few late py veinlets	G N	ANDS			QSP	P	5													
328.9	330.3	as from 325.2-327.9	K	VALT			KP	P	3													
330.3	331.8	as from 327.9-328.9	G N	ANDS			QSP	P	5													
331.8	333	as from 325.2-327.9	K	VALT			KP	P	3													
333	336.4	75% quartz veins, mm to dcm scale, variably deformed, cross-cutting. Wall rocks heavily QSP altered, pyritic. Thicker qtz veins are crackled, with late py>cp	G	QTVN			QSP STW	P	5													
336.4	339.1	as from 325.2-327.9. Scattered coarse Mt. Vague dull pink-red-purple hue in patchy zones may reflect potassic alteration	K	VALT			KP	P	4													
339.1	342.5	40% qtz veins, QSP altered wall rocks	G	VALT			QSP STW	P	5													
342.5	346	as from 325.2-327.9	K	VALT			QSP	P	4													

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
346	347.6	as from 339-342.5	G	VALT			QSP STW	P	5													
347.6	348.6	as from 325.2-327.9, some Mt	K	VALT			QSP	P	4													
348.6	349.3	50% qtz veins, 20% py	G	QTVN			QSP STW	P	5													
349.3	413.7	black to dark green chl-biot-mt-py altered (potassic), irregular, deformed mm-cm scale qtz veins	K	VALT			KP	P	4													
413.7	418	Massive to diffuse, vaguely granular intrusive texture. Light pinkish Kspar flooding around qtz-mt veinlets.	B	VALT			KP	P	4													
418	422	as from 349.3-413.7 Schistose, some shearing, deformed veinlets	G N	VALT			KP	P	4													
422	423.2	Intensely deformed zone - syn-mineral shearing? Very deformed cm scale qtz veinlets with py, cp. QSP altered matrix	K	VALT			QSP	P	4													
423.2	427.5	as from 349.3-413.7 Schistose, some shearing, deformed veinlets	K	VALT			KP	P	4													
427.5	430	schistose, chl-ser-py altered volcanic	G	VALT			CL	P	4													
430	438.1	mostly chl-ser-py altered tuff, some preserved intervals of Mt rich potassic alteration as from 43.7-418	G N	VALT			CL	P	4													
438.1	440.7		G N	VALT			CL	P	3													
440.7	441.9	Fault zone - several cm gouge intervals. Mostly intensely sheared, bleached QSP altered rocks and deformed veinlets	G N	FLTZ			QSP	P	4					fl		60						
441.9	446.1	moderately schistose tuff, homogeneous texture. Dark, mm scale angular fragments aligned with foliated QSP altered matrix. Dissem py, cp assoc. with scattered cm scale qtz veinlets	G N	VALT			CL	P	5				50									
446.1	448.7	Hybrid volcanic or intrusive altered rock? Mt rich as from 413.7-418	G N	VALT			KP	P	4													
448.7	453	as from 441.9-446.1	G N	VALT			CL	P	5													
453	455.5	as from 446.1-447.8. Mt rich	G N	VALT			KP	P	4													
455.5	464.1	as from 441.9-446.1. Homogeneous fine tuffaceous texture. Several cm to dcm scale qtz-sulph veins at 35 to 45d to CA with cp	G N	VALT			CL	P	5													

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
464.1	470.6	Mafic dyke, aphanitic to finely porphyritic, scattered small calcite filled amygdules, unaltered, unmineralized. Host rock shows cm scale chilled, bleached margins	N	DDRT																		
470.6	475.1	as from 455.5-464.1	G N	VALT			CL	P	3													
475.1	478.6	Schistose, moderately QSP altered tuff. E.O.H.	G N	VALT			QSP	P	4				45									

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	4.7	alteration makes primary texture diffuse, fine lapilli and ash fragments (mafic mineral fragments?) selectively pyritized. Schistose. Thicker qtz veins (1-4cm) have crackle filling and dissem py, minor cp	G	VALT	Sk	3	QSP	P	5				45									
4.7	8	mottled, spotted texture, dissem py, hornfels?	P N	VALT	Sp	4	IARG	P	4	QSP	P	3										
8	15.5	variably QSP altered	P N	VALT			IARG	P	3	QSP	P	3										
15.5	17.4	heavily veined zone - mo, cp in fine stringers, crackle fillings	G	VALT			QSP	P	5													
17.4	18.6		G N	VALT			IARG	P	4	QSP	P	1										
18.6	20.4		G N	VALT			IARG	P	3	QSP	P	3										
20.4	23.8	ragged py vein, 1cm thick, milky white qtz halo, roughly parallel to CA	P G	VALT			QSP	P	5	IARG	P	2										
23.8	30.8		P N	VALT			IARG	P	3	QSP	P	3										
30.8	35.2	Mostly green speckled (broken mafic minerals or fragments?), commonly aligned to foliation	P N	VALT			IARG	P	4	QSP	P	2	50									
35.2	37	qsp sections are bleached to pale green, schistose	P N	VALT			QSP	P	5													
37	43.9	Hornfels - spotted, mottled, diffuse texture, dissem and ff py, cp, sparse qtz veinlets	P N	VALT	Sp		IARG	P	4	QSP	P	1										
43.9	50.7	as from 30.8-37	P N	VALT			IARG	P	4	QSP	P	2										
50.7	51.5		P G	VALT			QSP	P	5	IARG	P	1	53									
51.5	62.9	as from 37-43.9, variable intensity. Py-chl typically occur together in small clusters	P N	VALT			IARG	P	4	QSP	P	3										
62.9	62.91	fault gouge, also 2mm at 66.3@70d												fl		45						
62.91	68.4		P G	VALT			QSP	P	5	IARG	P	2										
68.4	72		P G	VALT			QSP	P	5	IARG	P	2										
72	87.3	hornfels volcanic, foliated diffuse texture, vaguely tuffaceous, very broken core from 76-79,79.5-85	P N	VALT			IARG	P	4	QSP	P	4	50									
87.3	92.5	pyrite selectively replaces darker lapilli and ash fragments, which are aligned with foliation. Py-qtz veinlets	P G	VALT	Sk		QSP	P	5	IARG	P	1	50									

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
92.5	93.7	as from 72-87.3	P N	VALT			IARG	P	5	QSP	P	3	55									
93.7	96.2	more intensely veined, pyritic. Veins are ragged, sheared, discontinuous, deformed	P G	VALT			QSP	P	5	IARG	P	1										
96.2	101.5	veining increasing with depth, crackle filling py in +1cm thick veins. less foliation.	P N	VALT			IARG	P	4	QSP	P	3										
101.5	106.4	Massive, fine grained to vaguely	N	VALT			IARG	P	4	PR	P	2										
106.4	111.6	texture gets more diffuse to vaguely speckled	N G	VALT			QSP	P	4	IARG	P	3										
111.6	117	variable texture, diffuse spotted to distinctly speckled	P G	VALT			IARG	P	4	QSP	P	3										
117	138	magnetic unit - distinct diffuse almost granular or spotted texture due to hornfelsing of andesite (possibly fine diorite??) Rarely tuffaceous texture apparent. Qtz veining in py decreases with depth, magnetite is disseminated, in coarse irregular clots or replacement nuclei, a few qtz-mt veinlets.	G	VALT	Sp		PR	P	4	IARG	P	2										
138	143	as above, core is very broken up	G	VALT			PR	P	4	IARG	P	2										
143	199.7	Moderately altered lapilli tuff, mostly IARG with patches of mod-modstg QSP. Generally weak chalco, scattered patches of magnetite, vein like. Lapilli are completely replaced/altered to chlorite. QSP increases in intensity and frequency down hole.	G N	VALT			IARG	P	3	QSP	Pch	2	48	fl	0.1	60				5		
199.7	216.3	Moderately altered tuff (lapilli?), predominately QSP alteration with lesser IARG/CL. Weak overall qtz veining, traces of moly plus weak chalco. Significant shearing/fracturing in the first 4-5 meters of this interval.	N G	IVOL			QSP	P	3	IARG	Pch	2	50	fl	0.1	85	vn	0.2	75	5		
216.3	224.1	Intermediate tuff with mod IARG (chlor>ser) with lenses of wk-mod QSP. Continued wk qtz vning, increasing sulfides, mostly pyrite, and increasing occurrences of moly. Wormy qtz vning plus foliation "parallel" vns.	G N	IVOL			IARG	P	4	QSP	Pch	2	45							5		
224.1	229.3	Intermediate tuff with mod QSP, slight increase in Qtz vning and chalco, and moly. Traces of sphalerite noted in some qtz vns.	G	IVOL			QSP	P	4				45							5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
229.3	247.8	Intermediate tuff with mod IARG and .5-1.5m intervals of QSP mixed in. Qtz vns vary from .2cm-25cm thick, most running parallel to sub-parallel to foliation. Increase in Moly content, and sporadic Sp.	N G	IVOL			IARG	P	3	QSP	Pch	3	40							5		
247.8	251.3	QSPStk, significant increase in quartz veining and moderate increase in sulfides. Patchy chlorite and scattered as accessory mineral in some qtz vns.	N G	IVOL			QSP STW	P	5	CL	Pch	2	50	vn	0.5	50				5		
251.3	256.2	Tuff possibly ash or fine lapilli, with chlorite and spotty qsp alteration. Quartz as discontinuous blobs/breccia/replacement chunks. Traditional veining increases lower in section.	N W	VALT	Sp	3	CL	P	3	QSP	PD	2	46							5		
256.2	269.6	Tuff, mod chlorite alt with patchy/poddy IARG. Sparse qtz vning, qtz crackled in most veins. Wk pyrite, mod cpy. Occ qtz/iron carbonate vn, late stage.	D N	VALT	Eq	4	CL	P	3	IARG	Pch	2	60							5		
269.6	333.6	VU, w/ QSPStk, 60-85% qtz vning cut by a few late stage qtz-carb/chlorite vns. 5-9% pyrite, .4-1.1% cpy and traces of moly.	G,W	VU	Ck	3	QSP STW	P	5				50							5		
333.6	335.1	NREC		NREC																		
335.1	376.2	See above, at about 357m moly picks up (or thats when I caught on)	G,W	VU	Ck	3	QSP STW	P	5				45							5		
376.2	377.9	Diorite Dike with minor late qtz/carb/chlor vning	D N	DDRT																		
377.9	388.2	VU w/ QSPSTK as above but now with a bit of CL showing. Gradational contact at bottom of unit.	G,W	VU	Ck	3	QSP STW	P	4	CL	P	1	55							5		
388.2	399.6	intermediate tuff with significant qtz vning, but not generally above 60%. Chlorite concentration increasing with depth, grad contacts	A N G	VALT	Ck	2	QSP	P	3	CL	P	2	50							5		
399.6	417.6	intermediate tuff +- lapilli, chlorite>QSP qtz vning decreasing with depth as are sulfides esp pyrite. Qtz vning becoming wormy. Moly continues	A G N	VALT	Wm	2	CL	P	3	QSP	Pch	2	50							5		
417.6	424.2	QSP increases Chlorite decreases, increase in qtz vning, weak increase in sulfides.	A N G	VALT	Wm	1	QSP	P	3	CL	P	2	55							5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
424.2	472.7	Intermediate tuff +- lapilli and zones esp in last 20 meters of coarser equigranular tuffs. Chlorite with patchy very weak QSP. Pyrite 1-5%, weak chalco, some blobs of chalco in late stage qtz/carb vns. Variable but locally sig moly continues. EOH.	A G N	VALT	Wm	1	CL	P	3	QSP	Pch	1	60							5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	5.8	Casing and overburden		OVBD																		
5.8	22.6	Silicified volcanics. Local lapilli textures. Hem = 4 down to 11.0m. Py to 1% below 11m. Increased hornfelsing below 19m. Heavily fractured throughout.	D N, G	VUTF	Fo	1	SIL	P	4	SIH	Pch	3		fr	20					2	G	1
22.6	45.2	Gry-pink granitic intrusive. 2-4m stretches w/str hematization of matrix. Goe on fractures. 0.5-1% Py as blebs + vnlts. Mod late stage qtz +qtc vnlts. Locally ghosting of feldspar phenos. Tr CuOx on fracs.	G P	GRAN	Mo	3	SIH	P						stv	8					3	H	2
45.2	52.6	Volcanis w/str SIH overprinting. Oxides on fracs, sulphides as blebs + stringers. Locally pinkish overprint. Abdt fine x-cutting Goe vnlts	D G, N	IVOL			SIH	P	4											4	G	1
52.6	68	Hornfelsed volcanics. Locally .5-1m zones of granitic intrusive below 64m. Wk Goe on fracs. Abdt fine stkwk late qtz+qtc vnlts. Minor CuOx on fractures	G, P G	IVOL			SIH	P	3	SIH	Pch	4								4	G	1
68	68.93	Fault zone. Upper 35cm = clay alt'd oxidized mylonite. Volc hosted. Late carb vnlts. CuOx on fracs	D N, B	FLTZ	Fo	2							60							2	G	3
68.93	86.25	Lapilli tuff. Weakly foliated/lapillis aligned. Weakly hornfelsed. Abdt late qtc vnlts. Wk oxides on fracs. Tr CuOx on fracs. Blocky - rubbly	D N, N	VULT	Fo	2	SIH	P	2				70							4	G	1
86.25	171.9	Mod-strongly hornfelsed volcanics. H-felsing increasing below 120m. Locally tectonic bxa textures. Sulphides increasing below 103m., as vns and clots, to 4-6% Py, Tr-0.1% Cpy. 3-5m zones where Sih = 3. Minor Dk purp. Hem below 169m	K, D G	VU	Mo	2	SIH	P	4	SIH	Pch	3								5		
171.9	179.9	Dk greenish grey - grey hornfelsed volcanics. "Transition zone"?? At base of middle plate. Locally wk patchy ser alt'n. Locally reddish hematized granitic stringers. ~ 3% diss. Py. Late stage qtc stringers / vnlts. Ser alt'n increasing in last 1.5m.	D G, G	VU			SIH	P	4	IARG	Pch	1								5		
179.9	180.4	Mitchell thrust fault. Predom. Ser alt'd. Abdt milky qtz. Top 40 cm strongly "disked" fracture habit, then pea gravel sized rubble. Not a neat sheer zone, ie. May just be alt'n transition.	G	FLTZ	Fo	4	IARG	P	3				80	fl	30					5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
180.4	205.1	Mod-Str QSPSTW alt'd f.g.-m.g. volcanics. 30-70% Qtz as vns, splotches, etc. Sulphides diss. + often microveinlets in Qtz. Mod Chlor > Ser of matrix. Ser > Chlor below 199m as squirelly pale yel/grn ser alt'd matrix	A N, W	VU	Mo	3	QSP STW	Mo	3												5		
205.1	234.6	Pale greenish to yellowish green puke colored - highly ser alt'd VU. 20-40% Qtz vng w/local secondary kink folding. Sulphides as stringers + clots. Zones of pale yel-grn bedded textures similar to soft sed. Deformation. Mo predom. On greasy fol'n planes	G N, A N	VU			QSP	Bd	5	QSP	Mo	4								5		
234.6	256.3	Green, Lapilli to fine grained tuff. Wk fol'n textures. 5-10% qtz vns/m as squirrely 1-2cm crackled gry-wh vns. Generally weaker sulphides as vnlts, stringers and clots. Predominately chloritic alt'n to wk ser/Iarg locally as 20-40cm patches.	N	VULT	Fo	2	CL	P	3	IARG	Pch	2	45							5		
256.3	267.6	Pistachio grn, weakly foliated, brecciated, strongly ser alt'd volcanics. Mottled, swirly textured. 10-20% squirelly core axis parallel veins to clots of Qtz w/laddered sulphide vnlts in the Qtz. 3-4% sulphides. Clay alt'n at 263-266.2m	A, Y N	VU	Fo	1	QSP	Mo	6											5		
267.6	284.5	F.g. andesitic tuff protolith. Moderate IARG alt'n. Pale grn locally yellowish grn. 5-10% Qtz as squirelly core axis parallel vns to 2 cm thick. Fol'n parallel + cross cutting sulphide stringers and veinlets.	A N	VATF			IARG	P	4	QSP	Pch	2								5		
284.5	356	M.g. Lapilli tuff. Wk-mod chlor alt'n. <10% qtz vng. Moderate sulphide vnlts + clots. Lapilli text. More evident below 301m. Low grade Au?? No discernable fol'n angle. 356.00m (1168 ft) = TD	N, D N	VATF			CL	P	3											5		

SEABRIDGE GOLD INC

KSM 2007 Drill Log

Hole ID: **M-07-28**

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1 intens	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	5.18	Overburden/Casing		OVBD																		
5.18	8.4	Dk grn w/minor yel-grn VU. Qtz absent to 6.6m, then up to 20% Qtz. Mod chlor + Mod QSP alt'n	D N, Y N	VUTF	Mo	3	CL	P	2	QSP	Mo	2								4	G	1
8.4	14	Qtz Vein. 80-95% Qtz; Squirrely-splotchy. Sulphide vns make up 5-7%, maybe 2-3% ser alt'd matrix. Some oxides on fracs from 10-13.5m	W, G	QTVN	Ck	3	QSP	P	6											4	G	1
14	24.1	60-80% Qtz in v. str. Qspstw'd volcanic. Massive to mottled/crackled Qtz. 5-6% Py, mainly stringers + vnlts. Mod Goe on some fracs	G, A N	VU	Ck	2	QSP STW	P	6											4	G	1
24.1	24.9	80 cm No rec.		NREC																		
24.9	25.3	f.g. Dior dike - Goe on fracs, ~ 1% Py as vnlts in last 10 cm	D N	DDRT	Ms	2	CL	P	3											4	G	1
25.3	25.8	As 14.0 - 24.1m., 70% Qtz., Goe on fracs	G	VU	Ck	2	QSP STW	P	6											4	G	1
25.8	26.6	80 cm No rec. Ground core and cave material in box		NREC																		
26.6	46	Massive QSPSTW w/70-90% Qtz. Goe on fracs, mostly at 38.5-41.5m. 5 - 8% Py as stringers + vns to 1cm., and disseminated. Minor Cpy +/- Mo. 5-30% gry ser alt'd matrix where visible. Mottled to crackled texture of Qtz, w/Qtz often cut by sulphides. Locally wk fol'n texture.	G, A N	VU	Ck	2	QSP STW	P	6											4	G	1
46	73.6	As above, but no oxides now. Locally 30-50cm moderately chlor alt'd zones @ 50.6 and 60.5m	G, A N	VU	Ck	2	QSP STW	P	6											5		
73.6	74.37	NREC, gravel at end of run		NREC																		
74.37	201.4	As above, Massive Qspstw with locally 10-30% ser alt'd buggered up matrix of volcanics. No textures of wall rock observable.	G, D G	VU	Ck	2	QSP STW	P	6											5		
201.4	213.1	greenish yellow to grn-gry Vu. 55-80% Qtz - Patchy, squirelly to semi massive. 5-10% pistachio ser alt'd matrix within 20-30% wk chlor alt'd volcanics	G N	VU	Wm	3	QSP STW	P	5	IARG	Pch	3								5		
213.1	231.3	Mod-str perv. Qspstw'd volcanics with +/- 60% Qtz. Lt grn - yel/grn ser alt'd matrix. 3-4% sulphides. Qtz is semi massive to wormy 0.5-2 cm vns. Sulphides as stringers + clots	G, A N	VU	Wm	3	QSP STW	P	5											5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1 intens	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
231.3	313.7	gry - pale grn, fine grained andesitic tuffs. No pronounced fol'n angle. Mod pervasive grey ser alt'n. Decreasing veining to 4-8% qtz as wormy to 45 deg. TCA 1 cm veins. 3-4% sulphides, now predominately disseminated. Locally swirly pistachio strong sericite bands + minor clays. Iarg = 3 at 275-290m	G, A N	VATF	Ms	2	IARG	P	4												5		
313.7	370.8	Andesite tuff. F.g - m.g., locally lapilli textures. Grn - lt grn, wk fol'n textures. 5-10% Qtz vns/m +/- 45 TCA to axis parallel squirelly veins. Moderate perv. Ser alt'n (Iarg) to weak chloritic. 3-4% disseminated + vein pyrite with ~ 2% Cpy and locally trace moly on fractures	N, G	VATF	Fo	1	IARG	P	3	QSP	Pch	1	50							5		
370.8	398.4	Light-pale grn xl tuff w/minor lapilli zones. 5-8 qtz vns/m totalling 3-5%, plus 3-5 late wh. Qtz/carb stringers/meter. 3-4% Py, dissem. + minor veining. Moderate pervasive IARG, ser +/- Py alt'n. Low silicic alt'n. EOH = 398.37m.	G N	VATF			IARG	P	4												5		

Hole ID: **M-07-29**

SEABRIDGE GOLD INC

KSM 2007 Drill Log

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	6.7	Overburden		OVBD																		
6.7	13.4	Fine grained tuff, mod-stg chlorite w/ wk-mod QSP (patchy), wormy qtz vn, plus qtz vns ~ parallel to foliation. Badly broken, poor recovery and partially oxidized.	D N, G	IVOL	Wm	2	CL	P	3	QSP	Pch	2		stk	50					4	L	1
13.4	21.9	Mostly same as above but almost no oxides and less broken.	D N, G	IVOL	Wm	2	CL	P	3	QSP	Pch	2		stk	70					5		
21.9	32.45	fine grained tuff increased QSP/less chlorite, stock work of narrow qtz veins continues plus late stage qtz/chlorite vns with coarse chalco. Foliation very indistinct.	G N, G	IVOL	Wm	3	QSP	P	4	CL	P	2		stk	50		vn	0.2	40	5		
32.45	46.1	QSP increasing slightly, qtz vning up, chlorite more spotty, still late stage qtz/chl/chalco vns some with possible sphalerite (clots of chalco 2mm to 6mm)	D N, G	IVOL	Wm	2	QSP STK	P	4	CL	Pch	2		stk	60		vn	0.1	65	5		
46.1	53.3	Diorite Dike	D N	DDRT																		
53.3	118.8	Back to mod-stg QSPSTK, chlorite increased again, sulfides variable.	D N, G	IVOL	Ck	2	QSP STK	P	4	CL	P	3		stk	60					5		
118.8	132.7	lapilli tuff, small lapilli, wk-mod QSP, wk CL, sig drop in pyrite, less sig drop in Chalco, qtz vning much weaker.	G N	VALT			QSP	P	2	CL	P	1	55							5		
132.7	149.7	Lapilli tuff, 1-3mm totally chloritized, plus pervasive CL and patches of weak QSP, scattered 1-5+ cm qtz vns, py>cpy, Magnetite present wk carbonate in some vns.	D N	VALT	Wm	1	CL	P	2	QSP	Pch	1	35	vn	10	45				5		
149.7	159.6	LT w/ chlorite plus weak Pot alt. Qtz vning reduces, fewer and narrower, wk py (.5-2%), wk chalco, mag	D N	VALT			CL	P	2	KP	P	1	50	vn	8	55				5		
159.6	160.1	Fault												fl	1	70				5		
160.1	163.8	LT w/ chlorite plus weak Pot alt. Qtz vning reduces, fewer and narrower, wk py (.5-2%), wk chalco, mag	D N	VALT			CL	P	2	KP	P	1	50	vn	8	55				5		
163.8	187.2	LT w/ Propylitic alteration, Chlorite, mag, carbonate, pyrite(wk), plus chalco. Small lapilli still fully chloritized. Wk qtz vning	D N	VALT			PR	P	2				45	vn	12	45				5		
181.5	181.7	Fault												fl	1	70				5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
187.2	199.4	LT wk-mod chlorite, vwk but increasing with depth KP, mag, chalco ofter greater than py, but both weaker more abundant coarse cpy, esp in late qtz/carb vning.	D N	VALT			CL	P	2	KP	P	1	50	vn	10	75	vn	0.5	50	5		
199.4	222	LT w/ wk-mod KP, and wk chlorite, sig increase in carbonate vning, carb changes from yellowish Iron carb to pink carb, still with chunky chalco in some of these vns.	D N	VALT			KP	P	2	CL	P	1	55	vn	5	52	vn	2	40	5		
222	230.2	LT w/ wk chlorite and patchy weak .5-2m QSP, increase in qtz veining and pyrite is QSP zones. Overall slight increase in chalco. Overall decrease in carbonate veining ecept for interval noted below. Lapilli increase in size over last 5-6m of interval with propylitic alteration bleeding up.	G N	VALT			CL	P	1	QSP	Pch	1	40							5		
230.2	234	zone of carbonate veining and "shearing", weak qsp					CARB	P	2	QSP	P	1		vn	2	55	vn	1	30	5		
234	265.3	same as above	G N	VALT			CL	P	1	QSP	Pch	1	40							5		
265.3	271.3	Diorite Dike	D N	DDRT			PR	P	2				55							5		
271.3	278.3	LT w/ wk propylitic alteration, including epidote. Wk qtz veining (.1-12cm wide), lower contact seems gradational. Generally weak sulfides py>cp but ratio is closing.	N G	VALT			PR	P	2											5		
278.3	300.3	Feldspar porphyry med grained, magnetite, k-spar, epidote and some late stage carbonate veining. Qtz veining wk to locally moderate. Locally strong chalco generally wk py .1-.4%.	A N, G	PPFP			PR	P	2					vn	3	70				5		
300.3	329.8	LT wk PR w/ CL, tr epi, tr mag wk qtz veining weak dis sulfides occasional veinlets.	N G	VALT			PR	P	2				40	vn	2	32	vn	2	70	5		
329.8	333.9	PPFP as above	A N, G	PPFP			PR	P	2											5		
333.9	336.5	LT wk PR w/ CL, tr epi, tr mag wk qtz veining weak dis sulfides occasional veinlets.	N G	VALT			PR	P	2											5		

SEABRIDGE GOLD INC

KSM 2007 Drill Log

Hole ID: **M-07-30**

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1 intens	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	3.04	Overburden/CASING		OVBD																		
3.04	14.7	Mod-strongly oxidized (perv. Goe + Jar on fracs) Volcanics. Lapilli textures, non silicified. No sulphides, no qtz vng	B, D B	VULT	Fo	1	FEO X	P	4											2	G	4
14.7	17.5	No recovery, lost water pressure also		NREC																		
17.5	28.45	As above, oxidized volcznices. Finer grained below 20m. Possible F.G. Dike at 21.5-25.25	B, N	VULT			FEO X	P	3											2	G	3
28.45	104	Hornfelsed volcanics. Mod-str perv. Silic'n. Abdt qtz microveining increased from 45-77m. Trace-2% qtz vns/2m. Wk sulphides generally. Locally 0.5% splashy Cpy clots. Frac zone w/mod Hem alt'n at 46-48.5m. Local Bxa textures at 56-76m. Trace flourite on vein margins @ 58.3 - 60.5. Wk-mod oxides on fracs.	D G, G	VULT	Mo	3	SIH		4											4	G	1
104	139.3	Similar hornfelsed volcanic. But no oxies now. Varying fine grained opaque to dark gry/blk w/healed fracs. Bxa textures locally	G, D G	VUTF			SIH		5											5		
139.3	164	Greyish feldspar porphyry. +/- 5% smeared, rectangular Fspar phenos in a fine grained matrix. Not Lapilli tuff. +/- 5 Qtc 1 cm veins/meter. 2-4% Py as clots + vnlts. Locally moderate Cpy. Fairly well un-silicically altered.	G	PPFP	Po	2	SIH		3											5		
164	194.5	Back into med grained volcanics showing wk fol'n textures. Increased milky carb. Veins to 8 cm thick plus 5-8, 1-2mm carb vns.Locally 50-100 cm zones with porphyritic textures. 10 cm mylonitic shear zones @ 183.95 plus 189.55. See notes on collar page why hole was abandoned.	G, D G	VUTF			SIH	P	3											3		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	8.84	casing		OVBD																		
8.84	11	Massive, fine grained andesitic tuff, foliated, this may be a boulder above bedrock?	N	ANDS			PR	P	1													
11	16.8	Massive andesite, variable silicification and bleaching associated with thin fingers of monzonite, purplish jasperoidal silicification, cut by white quartz veinlets. Late ragged calcite veinlets. Fine dissem cp>py, occasional Mt clots	G N	ANDS	Ap	2	SIH	Pch	3											4	L	1
16.8	24	As above with 5-10% irreg. porph.monzonite fingers, cm to 10cm, with haloes of bleached, silicification and quartz veinlets, cp>py, purplish staining in intrusive and silicified haloes. Fracture controlled oxidation	G	ANDS	Ap	2	SIH	Pch	4											4	L	3
24	34.6	As from 16.8 to 24. Qtz veinlets typically broken up, boudinaged, deformed	G N	ANDS	Ap	1	SIH	Pch	3											4	L	1
34.6	38.1	Sheared andesite - deformation increasing with depth. Possible sand/grit filled cavities due to slope failures	G N	ANDS	Ck		PR	P	3											4	L	2
38.1	39.3	Fault zone - sheared, foliated, oxidized, a few cavities filled with mud, grit	N	FLTZ	Ck		PR	P	3					fl						2	L	4
39.3	41	Sheared ANDS / VALT, texture mostly obliterated. Late ragged calcite veinlets	K	VALT	Ck		PR	P	3											4	L	4
41	55	VALT variably sheared, deformed; siliceous; late ragged calcite veinlets, clots, gashes	G	VALT	Ck		PR	P	1	QSP	P	1								4	L	1
55	57.3	Variably silicified	G	VALT	Ap		SIH	P	4	QSP	P	1								4	L	1
57.3	58	Fault zone (Mitchell)	G	FLTZ	Ap		SIH	P	3	QSP	P	3		fl						4	L	2
58	73.8	Sheared, foliated: veins and mineral fabric	N	VALT	Fo		PR	P	2	QSP	P	2								4	L	1
73.8	76.85	Foliated, chloritized, low vein density. Very fine pale grey sericitized? Grains gives speckled texture	N	VALT	Fo		PR	P	4				65							4	L	1
76.85	90	As from 58-73.8 with less veining and deformation. 10-30% qtz veinlets	G N	VALT	Fo		IARG	P	4	QSP	P	2								4	L	1
90	104	typical tuffaceous texture, dark green to black lapilli in foliated, altered matrix. Fewer and less deformed veinlets than above. Minor calcite	N	VALT	Fo		IARG	P	4	QSP	P	2	60							5		
104	105.9	Bleached, slightly vuggy interval	N	VALT	Fo		IARG	P	4	QSP	P	1								4	L	1

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
105.9	106	Fault zone - oxidized gouge parallel to foliation	N	FLTZ	Fo		IARG	P	4				70	fl			fl			5		
106	110.2	Core is broken up along foliation and vein boundaries; tr. Malachite	N	VALT	Fo		IARG	P	4											5		
110.2	113.2	Typical VALT texture	N	VALT	Fo		IARG	P	4											5		
113.2	113.3	Fault zone - gouge with crushed rock fragments, malachite	N	VALT	Fo		IARG	P	4								fl			5		
113.3	118.5	Typical VALT; a few MnOx coated fractures. 1cm fault gouge at 115.5	N	VALT	Fo		IARG	P	4											5		
118.5	122	Typical VALT; a few MnOx coated fractures.	N	VALT	Fo		IARG	P	4											5		
122	126.5	Typical light green ser-py-qtz altered, foliated VALT	N	VALT	Fo		IARG	P	4				65							5		
126.5	133.5	Sharp contrast to dark green chl-py-mt altered VALT, more intense and thicker qtz stockwork veining, commonly with thicker wormy veins subparallelt to foliation and dominant veinlet trend	N	VALT	Fo		CL	P	3											5		
133.5	138.7	Interval with about 70% quartz veins and stockwork veinlets, earlier mm to cm scale veinlets mostly parallel to foliation cut by thicker, wormy veinlets subparallel to CA, rare magnetite in qtz veinlets along with py and cp, a few late ragged calcite veinlets	N	QTVN			CL	P	3											5		
138.7	158.2	50% qtz stockwork veinlets and veins, a few late calcite-chlorite-qtz veins up to 5cm. Chl-py-mt alteration variable. Where intense, texture is massive, diffuse to aphanitic.	N	VALT			CL	P	3											5		
158.2	161	Intensely chloritic alteration, foliation, grainy texture	N	VALT			CL	P	4											5		
161	180	as from 138.7-158.2. 10-30% qtz stwk veinlets, intervals with deformed, buckled, broken up veinlets (due to brittle contrasts during shearing). Thicker veins(1-10cm) have haloes of pale green sericitic alteration	N	VALT			CL	P	5	QSP	V	2								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
180	192.2	as above, but with thicker, wormy qtz vnlets, crackles lined with sulphides, sub-parallel to CA. Typically 1-2cm with cp-mo-mt-py	N	VALT			CL	P	5	QSP	V	1								5		
192.2	194.5	strongly QSP altered haloes around well mineralized 20cm qtz vein with coarse cp, mo	N	VALT			QSP	P	5											5		
194.5	196.5	as from 161-180	N	VALT			CL	P	5											5		
196.5	200.4	as from 192.2 to 194.5, with cp-mo rich qtz vein from 197.2-197.4. Shearing focused around fault at 198.2-198.3	N	VALT			QSP	P	4											5		
200.4	200.5	fault gouge and grit	N	FLTZ																5		
200.5	200.9	as from 196.5-200.4	N	VALT			QSP	P	4											5		
200.9	222.9	variably chl-ser-py-mt altered with patchy QSP focused in zones of higher density and thicker veins. Non-QSP altered "core" areas are nearly black, mt'c, weakly foliated (small volume). Lapilli texture variably clear.	G N	VALT			IARG	P	4	QSP	Pch	4								5		
222.9	230.1	strongly foliated section, sheared, broken, deformed, boundinaged qtz veinlets, with mm scale calcite filled tension gashes parallel to vein orientation. Foliation angle varies from 45-60 at top to 65-75 at bottom of interval	N	VALT			IARG	P	4											5		
230.1	230.2	Fault, cavity	K	FLTZ																5		
230.2	232.3	Intensely sheared, deformed zone, with abundant fine dissem. Py, dark greenish-brown-black color	N	VALT			QSP	P	4	IARG	P	3								5		
232.3	233.2	as from 222.9-230.05 EOH		VALT			CL	P	4											5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1 intens	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	7.62	Casing to 7.62m		OVBD																		
7.62	28.7	Lt gry-grey w/30% oxidized, Str on fracs, f.g. tuffs, abdt late Qtc veining. Locally pink granitic zones to 10 cm. Mod hornfelsing. Microveined (qtc) giving crackly texture	B O, G	VUTF	Ck	2	SIH	P	3											2	G	3
28.7	97.6	Dk gry - blackish hornfelsed volcanics. Oxides on fracs now. Weaker Qtc vnlts. Mod-str SIH. Locally 10-20cm zones w/str patchy pyrite (generally where dark hem/intrusives occur). 10-20cm zones of strong-massive Magnetite at 64.7, 73.8, 78.1, 80.5, 84.2, 87.2, 91.8 meters.	G, D G	VUTF			SIH	P	4											4	G	1
97.6	119.9	Gry-lt gry hornfelsed/silicic f.g. tuffs. Locally tan/gry colored opaque looking. Mod whispy qtc vnlts 2-4 mm thick. Oxides on most fracture. Still upper plate	G	VUTF			SIH	P	3											4	G	1
119.9	128.7	Lt gry w/locally greenish sericite tinted feldspar porphyry with +/- 20% phenocrysts. Pretty well bleached out. Wk Qtc veining, w/increased larger 1-8cm veins. Decreasing sulphides, no oxides now.	G, A N	PPFP			SIH	P	3											5		
128.7	139.8	Lt gry weakly hornfelsed volcanics f.g. tuff protolith. Weak Qtc veining. Locally patchy magnetite zones to 20 cm, often with abdt Py. 20cm Dior dike at 128.95m	G	VUTF			SIH	P	2											5		
139.8	152	Back into bleached lt gry Fspar porph. Wk Qtc vng. Decreased sulphides vs the silicified volcanics below.	G, A N	PPFP			SIH	P	3											5		
152	217.4	Lt. gry-gry-Dk gry hornfelsed volcanics. SIH increased, locally 5-10cm hem zones after intrusives often with moderate magnetite. Less sulphides below 170m, as dissem. And clots. Wk Qtc vng. Locally wk ser alt'n predating silicic event	G, D G	VUTF			SIH	P	4	IARG	Pch	2								5		
217.4	223.9	lt gry Fspar porph. w/5-10% bleached / ghosty phenos. Wk sulphides w/locally 1-2 cm banded Py vns. Qtz vng absent. +/- 5% Qtc whispy vnlts/meter	G	PPFP			SIH	P	3											5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1 intens	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
223.9	234.7	Weakly hornfelsed / silicified volcanics. Fine grained w/wk milky gry qtz vng. Increased sulphides as vnlts, clots, diss. Increasing shearing + fracturing and decr. Silicic alt'n in last 1.4m	G	VUTF			SIH	P	2											5		
234.7	235	Mitchell thrust fault. Mylonitic shearing top 15 cm, then foliated, schistose rubble w/minor clays and sand from 234.85 to 235.0m	A N	FLTZ																5		
235	255.2	Lt gry-pale yel/grn volcanics. Fine grained, not showing fol'n. Weak milky Qtc veins to 2 cm. low sulphides as dissem. + clots. Low IARG alt'n. Locally 5-10cm ser banded zones. 2-5% Qtz vns by volume	G, A N	VUTF			IARG	P	2											5		
255.2	331.3	Andesitic xl tuff? F.g.-m.g., lt gry, non foliated. Wk perv. Qsp alt'n without the quartz. Locally 1-2 (1-2cm) Qtz vns/sample. Generally 2-5 Qtc wispy vnlts/spl. 3-5% Py + Tr-.1% Cpy as irregular vnlts, clots and dissem. Gry ser alt'n weak, not silicically altered, w/wk to no Qtz. 5cm clayey shear zones at 299.7m, 309.6m, 314.5m.	A G	VATF			QSP	P	2											5		
331.3	340.2	Lt - pale greenish, wk larg alt'd volcanics. Similar to above, but slight grn ser content increase. Qtz absent, 3 4% Py generally fine grained disseminated. M.g. tuffs	A N, A G	VATF			IARG	P	2	QSP	Pch	1								5		
340.2	364.5	Very lt gry/grn wk Qsp/larg alt'd f.g. to m.g. volcanics. Sulphide content increased as dissem., + large 1-2cm clots. Locally 2-4cm Qtz veins with strong Py. EOH 364.54 0n Aug. 4	A G, A N	VATF			IARG	P	1	QSP	P	1								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	12.19	Casing																				
12.19	14	Breccia - mm to cm scale, subangular qtz vein and silicified rock fragments in a rock flour/grit matrix, strong limonite staining (leached py?). Fault or HBX?	G	FLTZ	Ck		SIL	P	4													
14	33.4	Silicified volcanic - bleached to pale grey, fractured and crackled, sheared, tectonic or HBX?. Late mm scale, ragged qtz and qtz-carb veinlets. Pervasive to fracture controlled oxidation and leaching	G	VU	Mo		SIH	P	4													
33.4	37	As above, sheared, fractured, crackled texture	G	VU	Mo		SIH	P	4													
37	47	Aphanitic, cherty textured, mm to cm clots and veinlets of mt. Fine dissem py, minor cp. Blotchy pink-brown tinting near intrusive contact	G	VU	Ap		SIH	P	5													
47	48.4	Dyke of maroon porphyritic monzonite. Diffuse texture due to silicification, veining, shearing	R	PQMZ	Po		SIL	P	5													
48.4	55.4	Int. bleached, sheared, fractured, crackled texture. Mylonitic from 50.7 to 50.8. Some matrix material looks fluidized. Weak pink tinting	G	VU	Ck		SIL	P	4	QSP	P	2	80									
55.4	58	Fine volcanic tuff texture preserved, less silicification and veining	P G N	VATF			SIH	P	4													
58	62.18	Hydrothermal Breccia - silicified volcanic fragments in chaotic texture, patchy dark pyritic rich sections in matrix, brecciated and late unbrecciated qtz-carb veinlets, mm scale	G	PHBX	Ck		SIL	P	5													
62.18	63.5	Probably bleached aplitic dyke, pale grey-green matrix with mm scale, dark green angular fragments, ragged qtz and qtz-carb veinlets	P G N	FDYK			SIH	P	3	QSP	P	2										
63.5	64	as from 58-62.18	G	PHBX	Ck		SIL	P	5													
64	65.3	Contact zone, silicified, brecciated, PQMZ and host rock fragments, chaotic fracturing and veining	U	PQMZ	Ck		SIL	P	5													
65.3	82	Int. qtz veined, silicified, bleached, PQMZ	U	PQMZ			SIL	P	5													

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
82	123.3	Bleached, cherty, silicified volcanic or sediment, mottled and crackled texture, massive to vaguely foliated, silica and/or fspar flooding in upper 2m. Late, mm scale ragged calcite veinlets and gashes. Fine dissem py (no late veinlets). Also note a very fine grained, dissem, steely blue metallic sulphide, either moly, sph, or tetrahedrite?	P Y N	SEDS	Ap		SIH	P	5	QSP	P	1										
123.3	128.1	Bleached, silicified-sericitic altered rock, speckled with med. Grained dissem py, massive (not foliated), zone is probably locus of shearing. Possible fault at 125-125.1 at 40d to Ca	P Y N	VU	Sp		QSP	P	5													
128.1	134.5	As from 82-123.3, with patchy QSP altered zones	P G N	SEDS	Mo		SIH	P	5	QSP	P	3										
134.5	135.7	As from 123.3-128.1, speckled due to dissem py	P Y N	VU	Sp		QSP	P	5													
135.7	136.5	Mostly just silica-pyrite altered rock	G	SEDS	Ap		SIH	P	5													
136.5	146.4	QSP altered but not foliated. Massive, mottled texture, possible albitic flooding, Sulphurets style alteration. Possible vague remnant laminations	P Y N	SEDS	Mo		QSP	P	5													
146.4	151.8	Pale creamy yellow, aphanitic rock, possibly patchy albite flooding, mixed with QSP and silica-pyrite alteration. Late dark green-blue chl (or pyrophyllite?) lined fractures in albitic bleached sections	P Y N	SEDS	Mo		QA	P	4	QSP	P	2										
151.8	154.6	diffuse white feldspar phenocrysts in maroon tinted (hematitic) matrix. Veined, bleached; core is broken and brittle (some lost core). Minor dissem cp>py	U	PQMZ			SIL	P	3													
154.6	154.7	Fault Gouge, oriented at 45d to CA	G	FLTZ																		
154.7	157	Dark grey, aphanitic silicified rocks, grades into interval below	G	SEDS	Ap		SIH	P	5													
157	168	Intensely bleached, pale yellow-green QSP altered sediments and/or volcanics? (not foliated) Late mm scale ragged calcite veinlets. Some sheared, fractured core	P G N	VU	Ap		QSP	P	4	SIH	P	3										
168	175.5	Intensely bleached, sheared, crackled zone. Blotchy pink-brown stained fspar flooding? Late dark green-blue chlorite or pyrophyllite lined fractures	P G N	VU	Mo		CL	Fr	4	KP	P	3										

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
175.5	180	Bleached, silicified, aphanitic rocks, sheared, crackled to almost brecciated textures. A few cm qtz veins, late calcite	G	VU	Ap		SIH	P	5	QSP	Pch	2										
180	183.1	Similar to above, but intensely crackled to brecciated	G N	VU	Ap		SIH	P	5	QSP	Pch	2										
183.1	185.7	Silicification, bleaching, crackliing diminishes with depth. Tuffaceous texture becomes discernable	N	VATF	Ap		SIH	P	3	CL	P	2										
185.7	193.6	Variably altered zone - from blotchy, mottled, bleached silica-fspar flooding to dark green-black mt-py-biot (potassic), gradual changes over 10's of cm. Moderate crackling, rare veins. Late calcite mm gashes	K	VU	Ap		CL	P	4	SIH	Pch	3										
193.6	198	Grades into less altered, crackled, fine grained andesite with more isolated, smaller bleached silicified patches. Dissem py, minor cp.	D N	VATF			CL	P	3													
198	209.6	Bleached-silicified blotches, patches, diffuse boundaries, overprinting dark green-black, chl-mt-biot-py alteration with clusters and aggregates of coarse py, minor cp. Aphanitic, minor v.f.gr. Dissem py. Crackled texture.	G N	VU			SIH	Pch	4	CL	P	3										
209.6	211	Hydrothermal Breccia with chaotic texture, fluidized matrix, fine to pebble size altered clasts, contacts at 30d to CA, late chl	G N	PHBX			CL															
211	221.3	As from 198-209.6 - more crackle fracturing, less bleaching in silicified, aphanitic intervals	G N	VU			SIH	Pch	3	CL	P	3										
221.3	221.9	HBX as in 209.6-211, very ragged contacts, dark chl'c matrix	K	PHBX																		
221.9	225.6	moderately bleached, aphanitic, altered volcanic	G N	VU	Ap		SIH	P	4	CL	P	2										
225.6	228.9	as above, silicification diminishing, fine calcite in crackles and gashes	D N	VU			CL	P	3													
228.9	232.9	Aplitic dyke, felsic? Fine granular texture, clasts of silicified wall rocks, may be subparallel to CA	G	FDYK			SIL	P	3													
232.9	234.4	As from 225.6-228.9	D N	VU																		
234.4	240.3	Aplitic dyke as above. Light grey, fine duffuse granular texture, irregular fractures with chloritic haloes	G	FDYK																		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
240.3	251.6	Variably sheared and altered, patchy aphanitic silicified intervals, py-cp clusters, aggregates in dark green-black chl-mt-biot altered original rock	D N	ANDS			CL	Pch	3	SIL	Pch	3										
251.6	253.2	Intensely silicified, finely crackled zone with v.f. dissem py>cp	B	VU																		
253.2	259.7	as from 240.3-251.6, variable alteration, sheared chaotic texture. Two 5cm maroon PQMZ dykelets at 254.9 and 255.3. Mylonitic texture (fluidized dyke?) at 257.55-257.65 at 65d to CA	D N	VU			CL	Pch	3	SIL	Pch	3										
259.7	267.7	dull olive green to black, cherty hornfelsed sediment? Patchy black chl-biot-py altered preserved nuclei cm scale	D N	SEDS	Ap		SIH	P	5													
267.7	269.1	similar to above but with chaotic, patchy, coarse py clusters and aggregates and cm scale calcite breccia veinlets	D N	SEDS			SIH	P	5													
269.1	275.6	distinguished by dull olive-green, mottled calcareous bleaching	P G N	SEDS	Ap		SIH	P	5													
275.6	278.4	foliated, pyritic, mylonitic? intervals with late pink tinted, irregular and discontinuous calcite veinlets.	G N	SEDS	Fo																	
278.4	280.7	Variable textured, aphanitic, bleached hornfels or skarned sediments?, calcareous, scattered clusters and layers of coarse py, minor cp	D N	SEDS			SIH	P	5													
280.7	281.7	cherty textured, bleached hornfelsed sediment, mottled, crackled	K	SEDS																		
281.7	285.3	varicolored, pink-brown-dark green-pale yellow green, mottled, bleached hornfelsed or skarned rock, chaotic sheared texture, coarse clusters and aggregates of py, fine dissem py	G N	SEDS	Ap		SIH	P	5													
285.3	286.7	breccia with coarse py in matrix, tr. Mo, cp. Subangular clasts of sediment, variably altered, sheared contacts at 45d to CA	K	PHBX			PSBX	P	4													
286.7	299.6	massive to vaguely laminated, volcanic derived wackes or siltstones, epid-chl-py alteration in veinlets and pervasive	D N	SEDS			PR	P	4	SIH	P	2										

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
299.6	306.5	fairly sharp contact to bleached, crackled, mottled SIH altered sediments, clusters and patches of coarse py aggregates	P G N	SEDS	Mo		SIH	P	5	PR	P	2										
306.5	322.7	as above, interlaced with decimeter scale, black chl-biot-py altered intervals with cp. Paler, mottled textured intervals are calcareous	K	SEDS	Mo		SIH	P	4	CL	P	3										
322.7	333.3	zone of interfingered black biot-chl-py altered intervals with pale green-grey, aphanitic calcareous sediments. Remnant laminations, variably deformed. Some sheared intervals. Py clusters, minor cross cutting, fluidized? Breccia veins with heavy py. Ragged, pink tinted calcite veinlets, cm scale	N	SEDS	Bd		CAR B			PR												
333.3	336.5	Altered andesitic dyke? Bleached pale grey-green fine diffuse granular texture with dark green, ragged, chloritized phenocrysts, fine dissem and coarse clusters of py with cp	P G N	ANDS	Po		SIH	P	4	CL	P	1										
336.5	339.5	white, finely crystalline or marblized limestone, banded due to dark mm scale layers. Locus of shearing, crackling, and deformation. Laminations at 10 to 30d to CA, possibly fold axis? Abundant irregular calcite veinlets. Contact areas have a chaotic texture	W	CCSD	Bd		CAR B															
339.5	342.6	Sheared, foliated, bleached zone, probable fault	P G N	FLTZ																		
342.6	363.9	Massive, aphanitic, mottled silica-py altered rock, late calcite veinlets throughout. Silicified sediments or felsic volcanic?? Disseminated and fine crackle filling py throughout. Some pale-yellow-grey sericite in ragged, irregular fractures.	P G N	SEDS	Ap		SIL	P	5													
363.9	366	Sheared interval, foliated, crackled, to chaotic breccia texture, heavy py-ser. Decimeter scale irregular calcite veins, blobs, late		FLTZ																		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
366	379	Bleached silicified rocks, similar to previous intervals, more speckled texture due to fine dissem clustering py. A few crackled to weakly brecciated intervals. Lower contact is a foliated shear zone at 55d to CA.	P G N	SEDS	Ap		SIL	P	5													
379	386	Fine grained tuff or volcanic derived sediment, homogeneous texture. A few 4-5cm calcite veins. Scattered mm calcite gashes. Grainy textured, weakly phyllitic	P G N	SEDS	Sp		PR	P	1													
386	400.9	Pale grey, massive, aphanitic, homogenous, silica-py altered rock, massive to weakly fractured. Calcite veinets and gashes throughout. Fine dissem and veinlet py, crackle filling	P G N	SEDS	Mo		QSP	P	4	SIH	P	2										
400.9	419.2	Similar to above, but distinguishedby paler, siliceous or albitized intervals, speckled with dissem py. More shearing, chaotic crackling, brecciation due to contrasting competencies?	G		Sp		SIL	P	3	QSP	P	4										
419.2	425	Distinct pale-brown hue. Slicified, aphanitic, fine dissem py	B		Ap		SIL	P	5													
425	426.3	Sheared zone, abundant late calcite veinlets, gashes	G		Ap		QSP	P	4													
426.3	430.9	Massive, aphanitic, silica-py altered rock, minor ser, cp. Late calcite	G		Ap		SIL	P	5													
430.9	432.4	sheared, fractured zone, abundant calcite veinlets	G	FLTZ	Fo		SIL	P	4	CL	P	2	47									
432.4	438	Aphanitc, massive to diffuse mottling, silica-py altered rock	G	SEDS	Ap		SIL	P	5													
438	442	Sheared and fractured zone similar to above, abundant late calcite veinlets	P G N	FLTZ	Fo		CL	P	3	SIL	P	2										
442	446.2	Sheared, QSP altered, pyritic rock	G	FLTZ	Fo		QSP	P	3													
446.2	447.9	Vaguely porphyritic textured, with dark green irregular, mm scale chloritized phenos, maybe volcanic interval or mafic dyke	G N	DDRT	Po		CL	P	2				50									
447.9	452.5	massive greywacke or siltstone, some vague laminations at 46d to CA	G	SEDS	Mo		SIH	P	4				46									

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
452.5	454.2	hornfels sediments. Bleached, aphanitic, pale grey-green with irregular blotches of black biot-chl-py altered material, crackle textured. Med grained pyrite in irregular clusters, and disseminated. Some late veinlets and breccia fillings with waxy, dull grey green anhydrite?	P G N				SIH	P	4													
454.2	456.6	mostly as in 447.9 to 452.5	G				SIH	P	4													
456.6	457.8	py rich, siliceous, diffuse mottled texture, some anhydrite as above in matrix and late veinlets	G	PHBX	Ck		PSB X	P	4													
457.8	461.8	similar to above, but less shearing and fracturing, and less pyrite.	G	SEDS	Mo		SIH	P	4													
461.8	464.4	HBX as in 456.6 to 457.8	G	PSBX	Ck		PSB X	P	4													
464.4	468.8	spotted hornfels asfrom 452.5-454.2	P G N	SEDS	Ap		SIH	P	4													
468.8	481	mostly massive, aphanitic, silica-pyrite altered sediments, a few sheared, calcite veined intervals	G	SEDS	Ap		SIH	P	3													
481	481.4	HBX as in 456.6 to 457.8	G	PHBX	Ck		PSB X	P	4													
481.4	483.8	finely granular, siliceous, faintly laminated in places, some sheared, crackled intervals	N	SEDS			SIH	P	2													
483.8	486.1	Variably sheared, brecciated, green siltstone, chaotic texture (see photo)	K	SEDS			SIH	P	3													
486.1	489	similar to above, but with dark, brick-red hematite rich intervals, irregular patches	K	SEDS			SIH	P	2	HEM	Pch	2										
489	496	similar to above, but without hematitic intervals. Several narrow crackled, brecciated intervals	K	SEDS			SIH	P	1													
496	506.6	mostly massive grey aphanitic hornfelsed sediment, some patchy chloritic remnants. More crackling, brecciation towards bottom	K	SEDS			SIH	P	2	CL	Pch	1										
506.6	510.2	similar to above, more streaky, dark, chloritized laminae, patches	K	SEDS			SIH	P	2	CL	Pch	2										
510.2	512.1	Sheared, chaotic texture to brecciated, weak HBX. Coarse py, possible anhydrite		PHBX			PSB X															
512.1	517.9	massive, pale grey silica-pyrite altered sediments, late calcite veinlets	G	SEDS	Ap		SIL	P	4													

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
517.9	519.5	HBX with calcite, anhydrite?(dull grey-green, waxy soft mineral) matrix		PHBX			PSB X															
519.5	522.5	as in 512.1-517.8	G	SEDS	Ap		SIL	P	4													
522.5	523.6	varicolored, hornfelsed rock with chaotic crackling	N	SEDS	Ck		SIH	P	3													
523.6	525.5	as in 512.1-517.8	G	SEDS	Ap		SIL	P	4													
525.5	526.5	brecciated, fractured zone with calcite veining, chaotic texture		SEDS	Ck		CAR B															
526.5	527.1	laminated to aphanitic, dissem py, hornfels	P G N	SEDS	Bd		SIH	P	3													
527.1	527.4	sheared zone with py, chl, late calcite		FLTZ			PR															
527.4	533.3	massive to laminated siltstone or greywacke	P G N	SEDS			SIH	P	1													
533.3	540.3	shear zone, subparallel to CA, chaotic breccia to mylonitic texture, late irregular, blobby calcite veinlets	P G N	FLTZ			QSP	P	2													
540.3	542	Aphanitic to v.f. grained, massive siltstone with dissem py	G	SEDS	Ap		SIL	P	1													
542	546.7	similar to 533.3-540.3	P G N	FLTZ			QSP	P	2													
546.7	550.7	Weakly sheared, fractured zone, seds as in 540.3-542, dissem py	P G N	SEDS	Ck		SIH	P	2	QSP	Fr	1										
550.7	556.5	grey, bleached silicified sediments, mottled texture	G	SEDS			SIH	P	4													
556.5	561.7	mixed silicified, bleached zones with green, propylitic altered remnants	G N	SEDS			SIH	P	3	CL	Pch	2										
561.7	567.1	massive, aphanitic, pale grey silicified rock with dissem py	G	SEDS			SIH	P	4													
567.1	569.2	sheared, brecciated zone, chaotic texture, py-qtz matrix, late calcite		PHBX			PSB X															
569.2	574.2	as from 561.7-567.1, minor late calcite	G	SEDS			SIH	P	4													

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	1.5	Casing /ovbn		OVBD																		
1.5	10.4	Massive Quartz veining. 5-8% pyrite, chalco, chalcocite, possible bornite. Iron oxides heavy in fractures generally not bleeding out very far into matrix.	G	QTVN	ck	2	QSP	P	5					fr	0.5	35				4	J	2
10.4	28.9	Volcanic with strong chlorite and spotty strong qsp, 4-8% pyrite, cp + cc +- Bn, oxides not quite as heavy, stockwork veining but not qsp.	N,G	VU	ck	1	CL	P	5	QSP	Pch	4	40	stv	50	40	fr	0.4	60	4	L	1
28.9	30.05	Diorite dike	D N	DDRT																		
30.05	38.2	VU w/ qspstk, and spotty cl, 5-8% py, cp, cc, BN? Oxides most prevelant from 36-38.2 assoc with lots of fracturing/faulting	G	VU	ck	1	QSP STK	P	5	CL	Pch	2	50	fr	4	70				4	L	2
38.2	40.85	VU, strong CL w/ wk very spotty qsp. Stockwork veining continues, 2-5% pyrite, cp, weaker and weaker cc and bn.	D N, G	VU	Wm	2	CL	P	5	QSP	Pch	3	45	stv	20		fr	0.2	70	4	L	1
40.85	42	NREC																				
42	93.25	VU, strong CL w/ wk very spotty qsp. Stockwork veining continues, 2-5% pyrite, cp, weaker and weaker cc and bn. Malachite/chryscolla begins to appear.	D N, G	VU	Wm	2	CL	P	5	QSP	Pch	1	45	stv	20		fr	0.3	70	4	L	1
93.25	124.5	VALT, CL weaker than before, IARG wk-mod spotty, very local QSP espically around some larger qtz veins. Generally weak pyrite, .5-3%, highly variable Chalcopyrite, traces of malachite early in interval. Zones of magnetite, FeOx reducing with depth but present in some fractures through interval	G N	VALT			CL	P	3	IARG	P	2	50	stv	20	50				4	L	1
124.5	131.4	VALT, strong CL, weak qtz veining plus carbonate veining. Zone is heavily sheered and broken.	D N	VALT			CL	P	5				50							5		
128	128.6	NREC																				
131.4	151.2	VALT, CL mod-stg, IARG wk-mod spotty, moderate qtz veining, 2-6% pyrite, cp locally strong, wormy crackled qtz veining plus some later bull qtz, former has py and cp seams.	D N	VALT	Wm	3	CL	P	4	IARG	Pch	3	40	ft	0.05	60				5		
151.2	156.1	Late qtz-chlorite vein "parallel" to core axis, remobbed chalco in coarse blobs scatterd throughout. Qtz is brecciated.	N, W	FLTZ	Bx	2	CL	P	6					ft	1	0				5		

Hole ID: **M-07-34**

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
156.1	242	VALT, CL Mod, spotty IARG wk-mod, qtz vning slightly less, 2-6% pyrite, disseminated cp and in veins.	N G	VALT	Wm	2	CL	P	4	IARG	Pch	3	45	ft	0.1	60				5		
242	354	VALT, CL-Prop mod, magnetite both in matrix and in some qtz veins. Carbonate veining and filling some cracks in qtz veins, plus weakly present in some of the matrix. Stockwork qtz vns slowly decreasing with depth. NQ2-BQ at 258.76m.	N G	VALT	Wm	1	PR	P	4	IARG	Pch	2	45							5		
354	486.4	VALT, Prop mod, w/ v weak spotty IARG. Quartz veining contiously decreasing with depth, carbonate veining increasing slightly with depth. (carb white and pink), py varies from .4-3%, cp decreasing slowly with depth, much weaker below 400m. Moly increases to around 400, then drops off again. Epidote in very minor quantities seen, mag decreases after ~400 too. E.O.H.	N	VALT			PR	P	4	IARG	Pch	1	50							5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	6.3	Casing (some of the 1m of cored rock in casing may be bedrock)		OVBD																		
6.3	23.7	foliated, schistose, fine grained, speckled to diffuse textured, typical IARG altered fine tuff, ubiquitous dissem py. Scattered crackled qtz veinlets up to 5cm thick with late py-mo, minor cp. Also later cross cutting mm scale py veinlets with bleached sericitic haloes, then later coarse calcite veinlets. Qtz veins have haloes of QSP bleached in grey tones.	N	VALT	Fo		IARG	P	4	QSP	P	1	45							4	L	1
23.7	25	as above	P G N	VALT	Fo		QSP	P	4											5		
25	27.2	as above	P G N	VALT	Fo		IARG	P	4											5		
27.2	30.2	as above, 1 cm shear gouge parallel to fol'n at lower contact	P G N	VALT	Fo		QSP	P	3	IARG	P	2								5		
30.2	62.5	homogeneous IARG altered tuffs with intervals of bleached QSP in more densely veined intervals. Most py disseminated, rare veinlets. Crackles in qtz veinlets are pathways for sulfides. 2-5mm clay gouge layers at 35.65, 46.5, 57.2 parallel to fol'n	P G N	VALT	Fo		IARG	P	4	QSP	P	1								5		
62.5	62.8	Quartz vein and intensely QSP altered wall rock, crackle filling and dissem py, mo, minor cp. 2-5mm clay gouge layers at 69.2, 72.05 parallel to fol'n	G	QTVN	Ck		QTVN													5		
62.8	77.5	as from 30.2-62.5	P G N	VALT	Fo		IARG	P	4	QSP	P	1								5		
77.5	89.75	more schistose, core broken up along foliation planes. Some Mo smeared on fol'n planes. 5-10mm clay gouge layers at 79.25, 80.75 parallel to foliation. Mo+cp in crackled qtz veinlets	P G N	VALT	Fo		IARG	P	4	QSP	P	2								5		
89.75	90	sharp contrast to intensely bleached and veined zone, adjacent to near massive qtz below	P G N	VALT	Fo		QSP	P	4	IARG	P	2								5		
90	91.95	near massive qtz vein, extensive crackling hosting dissem and clots of py>mo>cp	G	QTVN			QTVN													5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
91.95	115	IARG alteration clearly overprints earlier chl-mt alteration, which still exists in remnant ragged patches and layers. Mo in veinlets and smeared on foliation planes. Qtz veinlets up to 5cm thick, crackled with sulphides. Blotchy cal-chl-qtz vein subparallel to CA from 110-111.5	P G N	VALT	Fo		IARG	P	4	CL	P	2								5		
115	120	shattered core, poor recovery. Breaks mostly on vein contacts and in vuggy veinlets. Some litho description as above	P G N	VALT	Fo		IARG	P	4	CL	P	2								5		
120	126	as from 91.95-115, veins gradually getting thicker with depth. Most are parallel or subparallel to foliation. Scattered late calcite veinlets	P G N	VALT	Fo		IARG	P	4	CL	P	2								5		
126	137.5	Same litho as above, but IARG overprint weaker. Tuffaceous textures still discernable. More Mt	N	VALT	Fo		CL	P	3	IARG	P	2								5		
137.5	139.3	Mostly massive qtz vein, strongly crackled with py>>cp, mo, mt, vein is parallel to foliation	G	QTVN			QTVN													5		
139.3	141	as from 126-137.5	N	VALT	Fo		CL	P	3	IARG	P	2								5		
141	152	as above, but shattered core, poor recovery	N	VALT	Fo		CL	P	3	IARG	P	2								5		
152	158.9	typical tuffaceous texture, dark mm scale, subangular shards, chl altered, generally aligned with foliation, matrix is paler and very fine grained, pale chlorite to green sericite altered with ubiquitous fine dissem py. Abundant Mt, as disseminations, diffuse clusters, and in qtz veins. Some py replaces Mt	N	VALT	Sp		CL	P	4	IARG	P	1								5		
158.9	159.7	70% coarse cal-chl-qtz veins and blobs, minor coarse cp	W	QTVN																5		
159.7	165.7	as from 152-158.9	N	VALT	Sp		CL	P	4	IARG	P	1								5		
165.7	168.6	diffuse, coarse granular texture, almost intrusive like, due to silica and kspar flooding? Pale green to brown to pink tinting	N	VALT			KP	P	3	IARG	P	2								5		
168.6	209.3	typical tuff with qtz stockwork veinlets, increasing in density and average thickness with depth. Thicker veins (5-10cm) with crackle controlled py, mt, cp, tr mo, generally parallel to fol'n. Scattered cm scale coarse cal-chl-qtz veinlets	N	VALT	Sp		CL	P	4	IARG	P	1								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
209.3	209.4	Fault breccia, angular clasts floating in lt. healed (qtz cemented) green rock flour/grit matrix, 45d o CA.	A N	FLTZ																5		
209.4	211.1	typical QSP altered, intensely qtz stockworked interval - haloes a 2-3cm qtz py vein subparallel to CA	A N	VALT			QSP	P	5	CL	P	1								5		
211.1	217.4	as from 168.6 to 209.3, minor vein controlled KP alteration stronger towards lower part of interval.	D N	VALT	Sp	1	CL	P	4	KP	P	1								5		
217.4	235.1	VALT with diminishing KP alteration, scattered late calcite veinlets, mildly sheared. Late anydrite coated fractures.	N B	VALT	Mo	2	KP	P	3	CL	P	2								5		
235.1	235.9	Magnetite breccia, hbx with mostly magnetite matrix, large angular clasts of mostly chl-mt altered wall rock, some epidote, calcite	K N	PHBX			PR	P	4											5		
235.9	248.1	Intensely KP altered volcanic, 5-15% Mt, bleached, diffuse granular texture, like coarse intrusive but probably hydrothermal. Limited QSP haloes around cm scale qtz-py and py veins, veinlets. Well mineralized interval. Kspar as pinkish flooding adjacent to some qtz-sulfide veins, some pervasive flooding	N B	VALT	Mo	1	KP	P	5	CL	P	2								5		
248.1	267	Intensely veined, bleached, QSP altered zone, superimposed on earlier KP. Fracture-veinlet controlled. Late anhydrite coats some fractures and veinlets	A G N	VALT	Ck	1	QSP	P	5	KP	P	2	40							5		
267	280.4	intesnse QSP with minor chlorite, strong vning, with some intervals qspstk, late carbonate veins. Sulfides 6-11%, lesser in chloritic zones.	P N, G	VALT	Ck	1	QSP	P	5	CL	P	2	40	stv	50					5		
280.4	283.6	valt, strong chlorite alt, spotty qsp, weaker qtz and sulfides	D N	VALT	Wm	1	CL	P	4	QSP	Pch	3	45							5		
283.6	304.9	Typical tuffs with QSP to QSPstk locally, strong overall, with moderate patchey chlorite, qtzvning is reduced in CL areas, locally strong chalco.	D N, G	VALT	Wm	2	QSP	P	4	CL	Pch	3	40	stv	40					5		
304.9	315.8	QSPSTK, almost solid qtz locally. 6-10% pyrite, disseminated and in veins. Cpy dis, local mag and traces of moly	A G	VU			QSPSTV	P	5				45	stv	100					5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
315.8	319.1	Valt, strong chlorite, patchey qsp, locally strong cp, py varies from 1-10%, qtz veing much reduced.	D N, G	VALT	Ck	1	CL	P	4	QSP	Pch	3	45	vn	20	45				5		
319.1	361	VU strong QSP, patchey CL and some stockwork vning of short runs (~2m). Generally strong pyrite, variable chalco, tr moly, some local silification	G	VU	Ck	1	QSP	P	5	CL	Pch	2	35	stv	60	35				5		
361	393.4	VU weaker QSP, more chlorite patches, increased late stage qtz/chlorite veins. Continued strong pyrite, qtz veining/percentage reduced.	N,G	VU	Wm	1	QSP	P	4	CL	Pch	2	40	stv	40	40				5		
393.4	415.9	Valt, moderate QSP, chlorite more pervasive but still weaker than QSP. Locally strong chalco, average sulfides lower.	N,G	VALT	Wm	1	QSP	P	3	CL	P	2	35							5		
400.5	401.3	breccia zone in qtz/sericite healed partially with iron carbonate.																				
415.9	433	Valt with Chlorite alteration and Potassic(KP) and weak zones of QSP. Mod-stg magnetite. Moderate qtz veining, 4-8% pyrite, locally strong chalco including some clots. Late qtz/chlorite veins cutting at 60deg CA. Qtz veins vary in size from 1mm to 30cm.	N,G	VALT	Wm	2	CL	P	3	KP	P	1	50	stv	25	50	stv	10	30	5		
433	460.3	Typical tuffs with moderate QSP and weak but stronger than before KP. Quartz veining has increased slightly, sulfides as well. Vein width varies from 1mm to 1.2m	D N, G	VALT	Wm	2	QSP	P	3	KP	P	2	50	stv	30	50	stv	10	30	5		
460.3	531.3	VU, QSP stockwork STRONG, 6-10% sulfides, 70-85% quartz veining, vein count varies from 40 to more than 100.	W G	VU	Ck	2	SPSTV	P	6											5		
531.3	573.7	As above, but with 10-40% volume of wall rock fragments (inter and intra vein material). Fragments are intensely pink feldspar-magnetite-chlorite-pyrite altered (KP). It looks like veins in fragments are part of massive vein complex rather than earlier stockwork veining. Fragments are often almost all replaced by pyrite. Some massive qtz material has a slight pinkish hue, suggesting silicification of earlier kspar flooding? Qtz is well crackled and infilled with py and cp, minor mo.	W G	QTVN			QSPSTV	P	5	KP	P	3								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
573.7	574.3	Fault zone, intensely sheared rock to mylonite, roughly banded or foliated at 50 to 70d to CA	D N K	FLTZ	My								60	fl		60				5		
574.3	583	typical Mitchell host volcanic, mafic tuff? Mm scale, angular, dark green (chl'd?) fragments in paler grey-green fine to aphanitic matrix. Homogeneous texture throughout. Variable kspar flooding of matrix. Weak to moderate stockwork veining, some crushed and boudined. Py>cpy, tr. Mo	D N K	VALT	Ms		CL2	P	4	KP	P	2								5		
583	596.5	As above, but without any kspar flooding in matrix	D N K	VALT			CL2	P	4											5		
596.5	603	zone of intensely deformed qtz veining. Veins are crushed, sheared, and boudinaged. Higher vein and py content than above.	D N K	VALT			CL													5		
603	607.4	As above, but with less deformation. A few late calcite veinlets	D N K	VALT			CL													5		
607.4	682.1	Massive hydrothermal qtz vein complex, aphanitic pale grey-white, int. crackled with infilling py and cp. Well mineralized, up to 1% cpy, 10% py, coarse growths at crackle junctions. A few black wall rock fragments encosed, mostly mt-biot/chl-py altered. Specular hematite > mt from 612-615 only. At least three sets of late, cm scale qtz veinlets cut original massive vein, first is same color, second is milky white, third is milky white, coarse with chlorite. Second two sets occasionally have open spaces with coarse qtz crystals. All have some cp. Note "disking" of core from 652.5-656.7 maybe due to drilling issues?, rock looks the same. From 663-666.4, irregular late py veins subparallel to CA.	W	QTVN	Ck	5	SPST	P	6											5		

SEABRIDGE GOLD INC

KSM 2007 Drill Log

Hole ID: **M-07-36**

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	4.88	Casing & overburden		OVBD																		
4.88	19.1	VALT, mod-strong CL/PR with Quartz stockwork, slightly wormy, 30-60 per meter, 1mm-12cm in width. Wk-mod magnetite, v wk cpy, 1-3% pyrite, strong iron oxides vugs/rotten qtz after sulfides.	N, G	VALT	Wm	1	CL	P	4				60	stv	45	60				3	H,L	2
19.1	19.75	Fault, oxides, mylonite/schistose, minor qtz	O R	FLTZ									55	fl	1	50				2	H	4
19.75	49.35	VALT, PR mod, cl, mag, wk carbonate, wk qtz veining, oxides continue but weakening slightly. Traces of malachite, <1-3% wk pyrite, v wk chalcopyrite.	N	VALT	Wm	1	PR	P	3				60	stv	15	60				4	L	1
49.35	52.9	Diorite Dike, one or two qtz veins.	D N	DDRT																		
52.9	77.11	VALT, pR mod, cl, mag, wk carbonate, wk qtz veining, oxides continue but weakening slightly. Traces of malachite, <1-3% wk pyrite, v wk chalcopyrite. w/ possible chalcocite. Some leaching? Oxides weakening below 70m. 66.77-67.12 Flt. EOH	N	VALT	Wm	1	PR	P	3				60	stv	10	60				4	L	1

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1 intens	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	0.85			OVBD																		
0.85	14	VALT, IARG3, CL2? Wk fine gr. Diss Py, scattered Qtz vns, wormy and foliation dependant. Some coarser Py in Vns and along fracs. No signif. Oxides. Wk late carbonate	D N	VALT	Wm	2	IARG	P	3	CL	P	2	50							5		
14	47.4	VALT, IARG4, CL1. Fine gr diss Py, coarser Py in some vnlts and fracs. Still wk Qtz veining, less wormy, more fol'n dependant.	N	VALT	Wm	1	IARG	P	4	CL	P	1	60							5		
47.4	47.5	FLT Zone, clay / Gouge	P N	FLTZ										Fl	1	50				5		
47.5	64.9	As above	N	VALT	Wm	1	IARG	P	4	CL	P	1	50							5		
64.9	111	VALT, IARG4, w/spotty QSP. Increased Py? Still Trof CL. Hw Qtz vng, Generally fol'n parralel. Wk Fol - banded texture at 35 deg TCA. Tr Hem along vnlts locally. 10cm clay zone @ 105.0m, and 15cm clay zone at 107.2m	N, N G	VATF	Fo	2	IARG	P	4	QSP	Pch	1	40							5		
111	143.3	grn-yel/grn-gry grn volcanics. IARG inreased to 5 w/out lt. gry ser alt'n now. +/-10 qtz vns/meter - gry ladder fractured, fol'n parralel. Minor shearing down to 114m. Decr. Sulphides, generally assoc. w/qtz vng.	N	VATF	Fo	3	IARG	P	5				45							5		
143.3	143.9	No Recov.		NREC																		
143.9	191.6	f.g. lapilli (locally) tuffs. Mod Qtz vng - fol'n parallel. Grn-yel/grm ser +/1 chlor alt'n. Locally 1-2m patches of predom. Wk QSP alt'n. QSP increasing towards end of interval. Sulphides still weak, diss + Qyz vn related. Locally 10-15cm gry qtz/silicic zones. At a76.7-177.05 = 35cm wh bull qtz vn w/splashy Cpy clots	N, G	VATF	Fo	2	IARG	P	5	QSP	Pch	2	45							5		
191.6	205.4	Coarser lappilli tuffs. Gry - gry/grn. Wk-mod Qtz vng. Evenly mixed QSP and IARG. Increased sulphides over above interval	G, N G	VALT	Fo	3	QSP	P	3	IARG	P	2	40							5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1 intens	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
205.4	278.9	Strong QSP alt'd tuffs, gry - lt. gry - Dk gry. 50cm to 2m zones of IARG=4. Qtz increasing to almost stockwk. Sulphides increased overall. Semi massive Qtz vn at 212.34 to 213.15m. 225.45-227.0=1.55m semi-massive Py flooding. 10-20cm grey clayey shear zones @ 233.4 and 237.6m and 244.35m.	G, D G	VATF	Fo	1	QSP	P	5	IARG	Pch	1								5		
278.9	311.7	yel - grn banded textured to zones of grey QSP alt'n. Sulphides slightly increased as dissem. Molly increasing, as locally vnlts w/qtz. QTZ veining decreasing as opaque fol'n parralel vns < 1 cm	N G, N	VATF	Fo	1	IARG	P	4	QSP	P	3	40							5		
311.7	340.3	Grey, locally greenish gry volcanics. IARG = 3, 10 - 20% pale opaque sericitized Qtz vns / sample totalling 5-8% Regularly tr. - 0.05% Molly on qtz vn margins as clots and streaks and ~0.1% Cpy. 30 cm clayey shear zone @ 331.3m, and 15 cm shear @ 339.65m	G, N G	VATF	Fo	2	IARG	P	3				45							5		
340.3	417.8	Weakly fol'd volcanics, locally lapilli textures, generally med. Grained. Wk IARG Alt'n, wk Qtz vng. 2.5m zone where CL = 2 at 358.5 and 373.4m. Sulphides weak, diss. > vnlts	G	VALT	Fo	2	IARG	P	1				50							5		
417.8	428.2	Grey weakly altered Lapilli tuffs. Weak foliation. 3-5% Py w/o visible Cpy. V. wk Qtz veining. Minor frac/flt @ 422.15. Somewhat mottled appearance.	G	VALT	Mo	1	IARG	P	1				50	Vn	3	50				5		

Hole ID: **M-07-38**

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1 intens	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	13.45	Casing / Overburden		OVBD																		
13.45	50.29	Andesitic tuffs, generally f.g. w/local 50-100cm Lapilli sections. 5-15 late carb/qtc vns/m. Sulphide diss > vnlts. Local frac zones +/- 50 cm thick w/dk Jar + goe on fracs. Wk-mod patchy magnetite, Cpy assoc w/Mt	N	VATF			CL2	P	3												4	J	1
50.29	52.1	No rec + Cave		NREC																		
52.1	144	As above. Sulphides decreasing, 0.5 - 1.5%. 2-8% Qtz vns. Still oxidized locally on fracs. 65cm Qtz vn @ 104.70m. 10cm clay zone @ 109.2m. 20 cm f.g. dike @ 132.9m. Fol'n parallel shearing from 133.4 - 138.5m. 20 cm shear zone > clays @ 140.2m.	N	VATF			CL2	P	3												4	J	1
144	201.4	Similar to above. Unoxidized now. Qtz vng increasing to 5-10% Sulphides still weak. Tr Cpy throughout. Locally tr Molly. Wk-mod magnetite, locally as clots. F.G. tuffs. @ 170-175m increased qtz vng parallel TCA. Highly fractured/rubbly at 194.4 - 200.4m.	N	VATF			CL2	P	3												5		
201.4	245.4	chlolitic altered volcanics w/patchy (10%) pink potassic zones. Locally KP alt'n = pervasive., Usually bands - clots. Magnetite increased, Cpy incr. to 0.2-0.3% Qtz vng % decreased slightly	N P	VATF	Mo	2	CL2	P	3	KP	Pch	2								5		
245.4	300.2	Coarser grained, chlor alt'd lapilli tuff. Qtz vng decreasing to 2-4/m. Still wk sulphides. Overall wk alt'n. Foliation more pronounced. Locally v. wk. Mt. Epidote starts at 256.2m. 50 cm section w/10-20% epi bands and diss. @ 296.3m., Wk (~1%) K alt'd feldspar phenos below 294.4m., Locally sheeted, streaky Mo on fracs. 300.21m = EOH on Aug. 27	N	VALT	Fo	3	PR	P	2				45								5		

Hole ID: **M-07-39**

SEABRIDGE GOLD INC

KSM 2007 Drill Log

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	6.96	overburden and casing		OVBD																		
6.96	11	andesite tuffs few lapilli, mottled appearance due to broken qtz replacement in first 2 meters. Moderate FeOx, hem, goe plus pyrite, chalco and pos mal. Sulfides dis and in qtz vns, and small blebs.	N	VATF			CL	P	3				50							4	H,G	2
11	11.58	NREC		NREC																		
11.58	12.3	Andesite tuffs few lapilli. Moderate FeOx, hem, goe plus pyrite, chalco and pos mal. Sulfides dis and in qtz vns, and small blebs.	N	VATF			CL	P	3				50							4	H,G	2
12.3	13.9	NREC																				
13.9	19.4	VATF w/ CL2(mag) wk qtz vning, wk sulfides, py>cp tr mo. Oxides begining to weaken slightly, mostly confined to fractures, including malachite	N	VATF			CL2	P	3				50	vn	5	50				4	H,G	1
19.4	20.65	NREC																				
20.65	27.5	As above	N	VATF			CL2	P	3				50	vn	5	50				4	H,G	1
27.5	108.4	VATF w/ increased qtz vning (# & width), wormy and displaced. More carbonate vning too. 20cm dike of ddrt at 38.3m. Lower contact is gradational.	N	VATF	Wm	2	CL2	P	3				50	vn	25	50	vn	10	70	4	H,J	1
108.4	112.2	VATF, IARG + CL2, significant increase in Mag, qtz vns about the same, sulfides about the same, oxides weakening but still present, also weak scattered signs of KP alteration.	A N	VATF	Wm	1	CL2	P	2	IARG	P	2	50	vn	15	50				4	H,L	1
112.2	147.8	Typical tuff (ashy layers & lapilli richer layers), w/ moderate IARG and wk perv KP. Increased sulfides and magnetite w/ locally heavy chalco. 1-4 late qtz/chlor vns/m some with blebs of chalco. Mod-stg qtz vning	A N,G	VATF	Ck	1	IARG	P	3	KP	P	1	50	vn	20	40	vn	2	50	5		
147.8	166.6	tuff w/ mod CL and wk patchey KP. Qtz vning slightly weaker along with sulfides with local exceptions. Veining more erratic, fewer late qtz/chlor vns, occasional late carbonate vn.	N	VATF	Wm	2	CL2	P	3	KP	Pch	1	50	vn	5	50				5		
166.6	172.3	IARG 5, VU, blasted rock, locally brecciated qtz. Sulfides increase, contacts gradational.	A N	VU			IARG	P	5											5		
172.3	173.8	VATF w/ weaker alteration weaker qtz vning and sulfides, mostly pyrite is weaker. Foliation variable from 40-50 to CA	N	VATF			CL2	P	2	KP	Pch	1	45							5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
173.8	175.3	NREC																				
175.3	189.6	Same as 172.3-173.75	N	VATF			CL2	P	2	KP	Pch	1	45							5		
189.6	189.7	FLTZ, VERY POOR RECOVERY	N	FLTZ																		
189.7	191	NREC																				
191	202	Same as 172.3-173.75	N	VATF			CL2	P	2	KP	Pch	1	45							5		
202	232	VALT, more and coarser lapilli in some areas. KP increases but still less than CL. Qtz and sulfides slowly weaken with depth, except moly which may be slowly increasing. Chalco > py in most cases.	N	VALT	Ck	1	CL2	P	2	KP	P	2	40							5		
232	257.4	typical tuff CL2 about same, KP lesser, sulfides about the same cp>py most of the time. Foliation very weak.	N	VALT	Ck	1	CL2	P	2	KP	P	1	40							5		
257.4	260.2	VALT variably IARG around 25cm qtz vn, increased sulfides py>cp.	A N	VALT	Mo	2	IARG	P	3	CL	P	1								5		
260.2	285.9	VATF, wk-mod CL2, v wk patchy IARG plus some wk KP. Slight increase in qtz vein count, but not size. Sulfides about the same. Still weak mag. Foliation is weak and variable. E.O.H.	N	VATF	Wm	1	CL2	P	2	IARG	Pch	1								5		

SEABRIDGE GOLD INC

KSM 2007 Drill Log

Hole ID: **M-07-40**

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1 intens	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	10.9	Mixed volc., and ppfp + rubble		OVBD																		
10.9	123	Dk grn f.g. volcanics, mod chlor. + magnetite alt'n. Mt in clots > Diss. 3-5 qyz vns/m, with +/- 5% by volume. Minor late stage Cb veining., Wk Jar + lesser Goe on fracs. 40cm bleached, ser alt'd zone @ 34.6m. 15 cm clay goop @ 53.0m. 5 cm clay + shear zone @66.95m. 50cm Dior dike @ 69.55m. 10cm grn clays + shear @79.25m.	N	VATF			CL2	P	3												4	J	1
123	199.3	M. g. tuffs - Lapilli. 1-3 qtz vns/m generally < 0.5cm thick. Wk Cb vng., Wk splotchy Mt. Rubble/frac zone @ 145-148.5m., Wk sulphides, locally Mo on fracs, and on Qtz margins. Similar to above, but unoxidized now.	N	VALT			CL2	P	2												5		
199.3	222.7	Fractured, rubbly, chlor altered volcanics. Wormy, disjointed Qtz veining. Sulphides low. V. Wk patchy Mt	N	VATF			CL	P	2												5		
222.7	233.6	F.G. Tuffs to lapilli., +/- 1% epidote. Wk Qtz vng., more competant down to 227m, fractured to 231.5m., then whole again	N	VATF			PR	P	1												5		
233.6	251.1	Intercolated weakly hornfelsed seds/ash tuffs with chlor. Alt'd m.g. tuffs. Soft sed def. textures locally. Wk mm scale Cb vnlts. No Qtz veining. 1-3% Py, Cpy absent. 251.14 = EOH Aug. 30	G N	VUTF			SIH	P	2												5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	6.75	some cored till boulders		OVBD																		
6.75	14	"cataclastite" - sheared, mylonitic zone of intensely crushed stockwork qtz veinlets, oriented parallel to foliation	G N	FLTZ	My	3	QSP	P	4	CL	P	1	50	shr						4	L	1
14	16.5	transitional zone from above to mostly unsheared volcanics, lower contact mostly sheared vein from 16.3 - 16.55	N	VALT	Tf	1	CL	P	2	QSP	Fr	1								4	G	1
16.5	28.29	Dark green-black, fine grained volcanic tuff, scattered wormy, crackled qtz veins up to 4cm thick, with py, minor cp, mt. Some shearing and crushed veins, wk fol'n but mostly massive. Fine Mt, cp in both veinlets and wallrocks. Shattered, incompetent core from 21-22.5	N K	VALT	Tf	1	CL	P	4											4	G	2
28.29	31.39	As above, but shattered, broken up core, poor recovery, oxidized fractures, minor mal	N K	VALT	Tf	1	CL	P	4											4	G	2
31.39	32.4	As from 16.5 - 28.29	N K	VALT	Tf	1	CL	P	3											4	G	1
32.4	50.2	Variably sheared, magnetitic. Most veins are deformed, boudinaged, broken up. Some late calcite gashes, stringers. Probable fault gouge, 1cm at 33.85, 60d to CA. 1-3cm vein subparallel to CA from 43.2-44.4. Cp, py finely disseminated in veins and wallrocks	N K	VALT	Tf	1	CL	P	4											5		
50.2	63.1	dark green-black, aphanitic mafic rock with distinctive speckled texture due to very fine grained, disseminated mineral. Strong chloritization along fractures, shear planes and qtz-calcite veins, epidote. Unmineralized, no pyrite Some oranged tinted coarse calcite blobs	N K	DDRT	Sk	2	PR	P	4											5		
63.1	82.5	Weakly veined, variably sheared, mineralized tuff. Late ragged calcite gashes, rare orange tinted blobs. A few well crackled, sulfide mineralized qtz veins. Cp, Mo common in wall rocks, thin disseminations on fractures (incomplete fracture coatings)	N	VALT	Tf	1	CL	P	2											5		
82.5	82.55	sharp faulted contact at 30d to CA	A N	VALT	Fo	2								fl						5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
82.55	114.3	pale grey-green, aphanitic, QSP altered rocks with distinctive ragged vugs, mostly lined with calcite. Rare qtz veinlets. Weakly foliated. Volcanic texture almost obliterated. Looks like weak vuggy silica alteration, HS style, but silicification is grainy, not solid. Ubiquitous, abundant very fine dissem py, common Mo coated fractures, traces of cp. 2-3% calcite veinlets, stringers. Core is very brittle, shattered, incompetent. Upper 3 meters is increasingly sheared towards faulted contact	A N	SEDS	Ap	1	QSP	P	4												5		
114.3	120.1	massive, bleached pale grey, lightly veined, QSP altered, foliated to schistose rock, maybe sediment or tuff? A few scattered, wispy and boudinaged qtz veinlets. Late calcite veinlets	G	SEDS	Fo	2	QSP	P	4				55							5		
120.1	126.2	As above, but with 20% decimeter scale, coarse milky white qtz veins, with grey sericitized wall rock fragments, some dissem and crackle fill py. Generally more deformation towards lower contact. Lower contact is sheared, brecciated at 45d to CA (healed0	G	SEDS	Fo	2	QSP	P	4				50							5		
126.2	128.4	variably sheared, veined hornfelsed sediments, aphanitic, olive green-grey	A N	SEDS	Ap	2	PR	P	2											5		
128.4	135.6	probably silicified qtz rich siltstone or wacke, fine grained to aphanitic, weakly crackled with fine qtz veinlets, local qtz flooding	G	SEDS	Ap	2	QSP	P	3	SIH	P	1								5		
135.6	144.3	as from 120.1-126.2	G	SEDS	Fo	2	QSP	P	3	SIH	P	1								5		
144.3	160.1	as from 126.2-128.4. Aphanitic sediments, vague bedding textures, dull grey-green tones	G N	SEDS	Fo	2	PR	P	2	QSP	P	1								5		
160.1	166.4	variably bleached, crackled, sheared zone, maybe approaching and HBX. Ragged, sharp contact with healed brecciation	G	SEDS	Ck	2	SIL	P	3	PSBX	Fr	1								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
166.4	175.3	variably bleached, crackled, aphanitic sediments, mottled hornfelsic texture, dissem py and clusters along ragged fractures. From 170.25-170.75 is a dark green, unbleached remnant. From 173.5-173.75 is a coarse calcite vein at 45d to CA with minor coarse cp	A G N	SEDS	Ck	2	PR	P	2											5		
175.3	184.6	similar to above, but moderately silicified and bleached to grey, more dissem py	G	SEDS	Ck	2	SIH	P	3											5		
184.6	187.4	intensely bleached, silicified, crackled zone, approaching an HBX. Late calcite veinlets	G	SEDS	Ck	2	SIL	P	4	PSBX	P	2								5		
187.4	197.8	grey, aphanitic, siliceous sediments, weakly crackled, minor qtz veining, dissem py, late calcite. Brittle, incompetent, shattered core. Lost core from 189.5-190.5	G	SEDS	Ap	2	SIH	P	2											5		
		Note: hole abandoned as Mitchell zone lithology and alteration not present. Also, hole is making water under pressure causing difficult drilling conditions.																		5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	2.13	casing and overburden	OVB D																			
2.13	12.8	tuff, seems typical of area, mostly ash with some lapilli. Weak-mod propylitic alteration with a few qtz viens and numerous late calcite vnlets. 1-3% pyrite + cp and oxides, limonite, not very strong, weak spotty mag and epidote.	A G N	VATF			PR	P	2				50							4	L	2
12.8	14.6	NREC																				
14.6	23.1	tuff, seems typical of area, mostly ash with some lapilli. Weak-mod propylitic alteration with a few qtz viens and numerous late calcite vnlets. 1-3% pyrite + cp and oxides, limonite, not very strong, weak spotty mag and epidote.	A G N	VATF			PR	P	2				50							4	L	2
23.1	26	Felsic dike? w/ propylitic alteration and silicification, upper contact is at 55deg approx foliation	A T	FDYK	Mo	1	PR	P	1											4	H,L	1
26	32.4	Tuff w/ propylitic alteration, stronger Epi & mag, v wk qtz veining (thin wispy) plus late calcite veinlets, sulfide weakening, esp pyrite.	N	VATF			PR	P	3				50							4	L	1
32.4	36.85	Transition zone PAND and tuffs mixed. Dominant alteration is Prop, with weaker HEM. Epidote and locally strong sulfides 4%.	N	VATF			PR	P	2	HEM	Pch	2	55							5		
36.85	56.55	PAND, variable crystal size, sometime porphyritic (feldspar) other times aphanitic. Some minor qtz veining, wispy, and late calcite vning also wispy. Tr oxides. Generally CL2 alteration (mag to 15%) w/ Hematite alteration. Dis pyrite and vnlets/fract fillings. dis chalco plus minor fracture filling.	D M	PAND			CL2	P	3	HEM	P	1								5		
56.55	70.3	PAND,still bimodel grain size. CL2 stronger, with patchey hornfelsing and weak hem. Increased qtz vning size and number, but may be late and not same as Mitchell style. Also late orange and pink carbonate vns.	D M, N	PAND			CL2	P	4	SIH	Pch	2		vn	2	60				5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
70.3	87.2	PAND pervasive propylitic alteration, loss of mag, increase in sulfides, esp pyrite (dis). Local strong silica due to hrnfls including bleaching, plus more overall SIH but still patchey. Grain size of porph varies from aph to 2mm. Occasional xenolithe.	A N, N	PAND	Po	2	PR	P	3	SIH	Pch	2		vn	4	60				5		
87.2	98.9	similar to 56-70 but xenolithes as weak PR alteration and HEM alteration, more pyrite than 56-70.	D M, N	PAND			CL2	P	3	HEM	P	2								5		
98.9	114.9	PAND w/ PR and SIH locally strong. Sulphides weaker in areas of strongest SIH, lower contact very gradational.	A N	PAND	Mo	1	PR	P	3	SIH	Pch	3								5		
114.9	118.2	VU strong SIH. Weak pyrite in first half then stronger. Strong in some fractures.	G	VU	Ap	3	SIH	P	5											5		
118.2	119.5	NREC																				
119.5	121.8	Variably altered PAND, highly fractured probably fault zone. Numerous late calcite veins. Lots of NREC.	N, G	PAND			PR	P	2	SIH	Pch	3								5		
121.8	123.5	NREC																				
123.5	125.2	Variably altered PAND, highly fractured probably fault zone. Numerous late calcite veins. Lots of NREC.	N, G	PAND			PR	P	2	SIH	Pch	3								5		
125.2	125.7	NREC																				
125.7	138.1	Variably altered PAND PR and SIH dominate but also HEM. Sulfides overall slightly weaker than before, occ late organish carbonate vein.	M, N	PAND			PR	Pch	3	SIH	Pch	3								5		
138.1	170	VALT or SARG, mostly aphanitic groundmass, dominately PR altered, with SIH and spots of KP. Sulfides vary but generally 1-2%, very fine grained dis. Minor late calcite veining, almost no qtz vns.	D N	SARG			PR	P	3	SIH	Pch	3								5		
170	179.6	increase in PR level, with stronger epidote and some brecciation. Some looks almost like soft-sed defrm. Increase in calcite veining, late pink and white some qtz vning. Sulfides generally up a bit with narrow 2-15cm bands of intense sulfides.	A N, D N	SARG	Mo	2	PR	P	4	SIH	Pch	1		vn	2	60				5		
179.6	192	Reduced PR alt, epidote almost gone, SIH increases, sulfides weaker, very fine grained py dominates	A N G	SARG	Mo	2	SIH	P	3	PR	P	2		vn	2	30				5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
192	196.3	VAAT? Prop alt, HEM, weak SIH, strong Mag, coarser sulfides	M, N	VAAT	Bd	1	PR	P	3	HEM	P	2	60							5		
196.3	205.5	sarg? Pervasive prop, weaker patchey SIH, and patchey HEM, weak carbonate veining, and even weaker qtz veining, very fine gr pyrite locally coarser. Scattered epidote.	N	SARG	Bd	1	PR	P	3	SIH	Pch	2	60							5		
205.5	208.5	PPFP, weak silica, qtz veining and later qtz/chlorite with few calcite veins. Coarse chalco and trace of galena	G	PPFP	Po	3	SIL	P	1											5		
208.5	234.8	SARG, increased epidote, v wk mag, perv SIH, locally strong, generally wk sulfides fn grained. EP and PR alt in general weaken over last 2m	A N	SARG			PR	P	4	SIH	Pch	3								5		
234.8	237	PPFP mostly finer grained, some coarse chalco	G	PPFP	Po	1	SIL	P	1											5		
237	243.6	SARG, w/ weak PR and wk SIH	A N, G	SARG	Mo	2	SIH	P	2	PR	Pch	1								5		
243.6	248.7	tuff? With increased PR, patchy SIH, shearing at 65-80 deg to Core axis, 3-10cm sections with increased pyrite around some shears, competent in between shears. More calcite and late qtz vning. Section messed up.	A N, G	SARG			PR	P	2	SIH	Pch	3		fr	2	65	fr	1	80	5		
248.7	251.3	incresed PR alt, lots of shearing/faulting shear zones, gange and clays wk sil in spots, poor recovery.	A N, G	SARG	Mo	2	PR	P	2	SIH	Pch	2		fl	2	60				5		
251.3	253.2	NREC																				
253.2	255	same as 248-251	A N, G	SARG	Mo	2	PR	P	2	SIH	Pch	2		fl	2	60				5		
255	269.2	varibably altered tuffs/seds patchey PR from 1-3, patchey SIH 1-4, variable sulfides, locally 10% (2-10cm) average ~1-1.5% and locally 0.5%. Flt at 262 and 262.4	A N, G	SARG	Bd	1	PR	Pch	3	SIH	Pch	3	65	fl	0.1	40				5		
269.2	270.3	NREC																				
270.3	314	Strong SIH with patchey PR in SARG, not much qtz vning, mostly weak calcite with some late qtz vning.	A N, G	SARG	Mo	3	SIH	P	4	PR	Pch									5		
314	321.1	SARG? Cooked buggered rock. Prop alt dominant, with weaker SIH lots of wispy calcite fillings, in weak breccia	A N, G	SARG	Mo	3	PR	P	3	SIH	Pch	2								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
321.1	331.5	PPFP, variably Propylitized, late qtz vning, and qtz/carb. Epidote locally strong, few narrow pyrite veins and nodules.	G	PPFP	Po	3	PR	Pch	2											5		
331.5	355.7	SARG, Strong SIH & PR including Epidote. Moderate increase in sulfides. Increasing chlorite with depth. Definite increase in MAG over last 4 meters with locally massive. Sulfides vary from 1-4%. Chalco weak, no significant veining. E.O.H.	A N, G	SARG	Bd	3	PR	P	4	SIH	Pch	3	40							5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	1	overburden																				
1	1.5	Nearly massive hydrothermal qtz veining and breccia, 80% qtz by volume with clasts and wispy inter-vein material of grey QSP altered volcanic. Ubiquitous fine dissem py, minor cp, mo. Also some dark steely blue-grey mineral which may be chalcocite partially replacing pyrite and cpy.	W	QTVN	Br	3	QTV N	P	6											4	J	1
1.5	10.5	As above, without oxidized fractures	W	QTVN	Br	3	QTV N	P	6											5	J	1
10.5	13	As above, some shearing focused on soft sericite altered intervals, minor oxidation on fractures	W	QTVN	Br	3	QTV N	P	6											4	J	2
13	23.7	As from 1.5-10.5, a bit less qtz and more sericitized, foliated wall rocks, a few scattered fractures with limonite coatings. Thicker qtz veins (10 cm) are well crackled with pyrite filling crackles.	W	QTVN	Br	3	QTV N	P	6											4	L	1
23.7	27.7	Intensely sheared, deformed, brecciated shear zone, with late decimeter scale coarse calcite-chlorite veins, chaotic foliation angles. Some pasty gouge and crushed zones	P N	FLTZ			PR	P	4	QSP	P	2		fl						5		
27.7	60	Semi-massive hydrothermal qtz veins, anastomizing, breccias, intensely crackled with py filling, ubiquitous dissem py, minor cp, mo. Est. 80-90% hydrothermal qtz. Scattered shear slips along grey sericitic altered, foliated intervals. A few late ragged py clusters along irregular fractures, tr. cp, mo	W	QTVN	Br	4	QTV N	P	5											5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
60	114.4	transitional from semi-massive hydrothermal qtz to intense QSPSTK alteration. Est. 40-60% hydrothermal qtz. Veins are mm to decim scale, crackled with py. Wall rocks are grey sericite-pyrite altered, minor amounts of blue-green micaceous mineral may be pyrophyllite? Veins are highly contorted, intricately folded, deformed, very difficult to make accurate qtz vein count. Minor cp, mo poss. cc (or sph, tetrahedrite). Patchy yellowish sericite increases with depth. Sericite altered wall rock intervals are locus of shearing due to competency contrasts with qtz veins rich intervals.	G	VU			QSP STW	P	6												5		
114.4	120	Semi-massive qtz veins and silicified rock, stockwork, shearing, deformation increase towards bottom.	G	QTVN			QSP STW	P	6											5		
120	121.3	Shear zone - broken up, clayey gouge coated fragments of grey QSP altered rock	G	FLTZ			QSP STW	P	6					shr						5		
121.3	121.7	Mostly coarse calcite-chlorite vein material	G	QTVN			PR	V	6											5		
121.7	132.4	Int. grey QSP altered, sheared rocks, with mangled, folded, crushed stockwork veining. Ubiquitous fine dissem py, minor mo=cp	G	VU			QSP STW	P	6											5		
132.4	132.9	Mostly coarse qtz and calcite-chl-py veins	G	QTVN			PR	V	6											5		
132.9	134.4	As from 121.65-132.4	G	VU			QSP STW	P	6											5		
134.4	139.9	Shear zone - broken up zones with clayey gouge coatings focused in QSP intervals surrounding qtz veins/silicified zones (competency contrasts)	G	FLTZ			QSP STW	P	6					shr						5		
139.9	144	As from 121.65-132.4, clayey/sericitic gouge layers, 1-2cm thick at 141, 143.3, 144m	G	VU			QSP STW	P	6											5		
144	146	More intensely foliated, less qtz stwk QSP	G	VU	Fo	4	QSP STW	P	6				50							5		
146	146.6	Fault gouge	W	FLTZ										fl						5		
146.6	149.2	Sheared, qtz vein rich interval as from 134.4-136.5	G	VU			QSP STW	P	6											5		
149.2	150	Fault zone at 070d to CA, white-grey gouge with crushed qtz fragments	W	FLTZ										fl						5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
150	163.7	typical int. QSP altered, schistose rock. Stwk is often crushed, mangled	G	VU	Fo	4	QSP	P	6				55							5		
163.7	174.2	transitional from QSP to IARG dominant alteration. A few 20cm thick crackled qtz veins, but generally weak stwk veining. Low cp<mo, ubiquitous dissem py, a few veinlets with bleached haloes	G N	VU	Fo	4	QSP	P	3	IARG	P	3								5		
174.2	182.1	typical IARG, bluey-grey/green, foliated, abundante fine to med. Grained dissem py, scattered qtz veins up to 3 cm, crackled with py	G N	VU	Fo	4	IARG	P	5	QSP	P	1	60							5		
182.1	182.2	Fault gouge with pasty grey moly?	G	FLTZ										fl						5		
182.2	224	as from 174.2-182.1, 1cm fault gouge parallel to foliation at 191.3, 194.6. Rare late calcite veins	N	VALT	Fo	3	IARG	P	4	QSP	P	1	60							5		
224	246.1	as above, slightly more grey QSP altn/bleaching, a few more 2-4cm crackled qtz veinlets. Shearing along qtz vein at 80d to CA. Rare late calcite veinlets	G N	VALT	Fo	3	QSP	P	3	IARG	P	3								5		
246.1	246.2	Fault Gouge	G	FLTZ			QSP	P	3											5		
246.2	253.5	As from 224-246.1, but several irregular blobs, veins, vein breccias of coarse milky qtz-chl, 1-10cm. 2cm fault gouge at 252.9	G	VALT	Fo	2	QSP	P	4	IARG	P	2								5		
253.5	254.5	Near massive coarse milky white qtz-chl vein	W	QTVN			QTV N	P	5											5		
254.5	254.9	Fault zone, gouge and sheared rocks	N G	FLTZ			QSP	P	5					fl						5		
254.9	261.4	Foliated QSP/IARG altered tuffs, homogeneous, cm crackled qtz veins with py, mo, some wormy	G	VALT	Fo	2	QSP	P	4	IARG	P	2	45							5		
261.4	272.3	similar to above, but more grey bleaching, less foliated, more massive. Fewer veinlets. More abundant and coarser dissem and ragged veinlet py. Also more abundant late cm scale white qtz-chl veinlets, pale green tinted, possibly some pyrophyllite?.	G	VALT	Ms	2	QSP	P	5											5		
272.3	277.7	Fault zone, gouge and sheared rocks, fractures roughly parallel to foliation	G	FLTZ			QSP	P	4	IARG	P	1		fl						5		
277.7	284.3	similar to 266.4-272.3, less schistose, more massive, speckling mostly due to abundant dissem and ragged vnlt py. Rare qtz veinlets	G N	VALT	Ms	2	QSP	P	4	IARG	P	1								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
284.3	312.7	similar to above, but more varitextured, mottled-aphanitic to moderately foliated, more pale yellow-green aphanitic sericite or illite, scattered cm scale qtz-chl veinlets		VALT	Mo	2	QSP	P	4	IARG	P	2								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1 intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	1.3	Overburden, not recovered		OVBD																		
1.3	22.3	Fine grained volcanics w/mod perv. Silicification due to hornfelsing. Abdt late crackly Cb veining. Locally mod Py. Qtz vng lacking. Upper plate Rx.! Locally minor Kp alt'n. @ 10.2-21m. Locally Dk Jar on fracs. Minor fault? Carb filled Bxa zone @ 21.4-22.3m.	G, G N	VUTF			SIH	P	4	CL	Pch	1									4	J	1
22.3	43.4	Unknown v.f.g. - f.g. volcanics w/mod pev. Silicification. Lost the shiny opaquish hornfelsed look, with more original textures visible. Carb. Veining about gone. Often Moly on fracs, wk Jar on fracs.	G	VUTF			SIL	P	3												4	J	1
43.4	53.55	Back into hornfelsed f.g. tuffs. Locally mod. Maroon hematized xenoliths to 3 cm. Crackled Carb vng returns. Fractured / rubbly @ 43.4 - 44.0m.	N G M	VUTF			SIH	P	3	HEM	Pch	1									5		
53.55	55.45	Fault zone - Mitchell thrust. 45cm greenish pale clays among grn ser alt's volcanics w/wk mylonitic textures. 5 cm dior dike @ 54.25m.	A N	FLTZ			IARG	P	3												5		
55.45	71.7	pale greenish volcanics w/mod wh qtz/carb. Veining. Locally fractured. Greyish mod-str IARG alt'n. 22cm massive Py @ 57.85m., 10cm clay/shear zone @ 69.4m., 5 cm msv Py @ 64.18m.	A N	VATF			IARG	P	5												5		
71.7	126	Similar to above but IARG dropped to 2. Less alt'n, less veining. Textures more visible - Lapilli tuffs. 8cm clay seam @ 96.6m., Moly commonly as smears on fracs and on qtz vn margins. Py diss>clots>vnlts. 25cm clay/flt zone @ 125.65m.	N	VALT	Fo	1	IARG	P	2				50								5		
126	168.6	pale green - greyish grn volc. IARG increased to 4. Banded/mottled appearance w/abdt. Tan/wh. Carb. + anhydrite veining which is increasing below 144m. Splotchy to banded dk chlorite locally. Rubbly / sheared zone @ 127.5 - 132m., 30cm anhyd. Vein @ 166.7m., 10 cm purple carbonate vein @ 167.9m.	A N	VUTF	Fo	2	IARG	P	4	CL	Pch	2	70								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1 intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
168.6	198	typical mod-wk IARG altered volcanics. Increasing gry perv. Ser below 187m., gry wormy qtz veining incr. also. 72cm X 4cm thick core axis parralel Py vn @ 190.55m., Wk qtz + Py filled shear zone @ 182.75-183.0m.	N G, N	VATF	Fo	2	IARG	P	3				50							5		
198	245.8	gry-lt. gry foliated volcanics w/wk perv. Ser alt'n. Distinct Qtz vng - v. wk. Fol'n parallel Py vnlts > diss. Py. 10cm Clay gouge @ 205.52m., and at 213.85m., 10cm clay + Qtz @ 220.1m.	G	VUTF	Fo	3	QSP	P	2				65							5		
245.8	269.9	grey - dk gry banded/foliated w/abdt pale grey ser. After qtz veined alt'd matrix. Qtz % increasing slightly, QSP alt'n., but qtz not too abundant 4-6%. Increased pistachio colored ser stringers below 245m. CHANGE to BQ at 255.41m.	A G, D G	VUTF	Bd	3	QSP	P	4				60							5		
269.9	285.6	Back into grn chlor/IARG wk alt'n. f.g.-m.g. tuffs, minor qtz vng. Wk cpy, wk-mod Py	N	VATF	Fo	1	IARG	P	2	QSP	Pch	1	50							5		
285.6	314.2	Greenish grey mixed v. wk. QSP + wk. IARG. 2-5% Qtz vng. Py vnlts > Diss. Not too interesting	G, N G	VATF			QSP	P	2	IARG	Pch	1								5		
314.2	416.3	Wk IARG + Wk Chloritic Alt'n., - boring grn unaltered f.g tuffs. 2-4% Py, tr CPY, 2-4% Qtz. Locally Mt + Spec hematite veinlets to 1 cm below 353m., 10cm violet anhydrite vein @ 358.7m., 5cm clay gouge @ 414.8m.	N	VATF			IARG	P	1	CL	P	1								5		
416.3	442.5	Similar to above w/slight increased IARG alt'n. Qtz vng increased. Banded texture w/fol'n parallel grn chlor/ser more abundant, still wk-mod	N, G N	VATF	Bd	2	IARG	P	2	CL	P	1								5		
442.5	500.7	4-6% Qtz veining in less alt'd grn-pale grn, wk CL-wk IARG alt'd volc. Tr-0.1% Cpy. Generally 2-3% diss. Py and on qtz vn margins. Locally tr Moly. 1.53m anhydrite vn (wh-buff-purp) with off white albite? Clots @ 450.15m. Alteration + Qtz veining increasing below 497m.	N, A N	VATF			CL	P	1	IARG	P	1								5		
500.7	535.2	gry-lt. gry mod QSP alt'd volc. Abdt (6-12) qtz vns/meter generally fol'n parallel < 1 cm wide. Anhyd + Qtz/Carb veining intermittent - 10 cm veins from 515.3 - 516.3m.	G, A G	VUTF	Bd	3	QSP	P	4				50							5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1 intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
535.2	571	Slight decr. In alt'n intensity. Qtz vng decreasing to 5-15% Less banded / qtz vn textured. Sulphides predom. Fol'n parallel. 22cm anhyd. Vn @ 542.0m., 554.25-554.82 = anhyd. Vn.	G	VUTF	Bd	2	QSP	P	3											5		
571	588.9	Less altered, 1-3% Qtz, Py still wk-mod. Locally minor pistachio ser stringers	G, NG	VATF	Fo	2	QSP	P	2											5		
588.9	614.4	Still wk Qtz, mod Py, but visually more altered. 2-8% tourmaline as clots and radial crystal habit. Leopard skin textured at 611-614.4m w/abundant pistachio ser. Banding.	G	VUTF			QSP	P	3											5		
614.4	646.1	Back into grey, monotonous volcanics w/wk QSP. 2-3% Qtz., Sulphides (Py) still @ 4-5% and generally tr-0.1% Cpy. Wk foliaed text. Niton shows big drop in Cu @ ~ 580m. EOH @ 646.14m Sep. 14, 2007	G	VUTF			QSP	P	2	IARG	P	2								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	4.57	Overburden																				
4.57	10	pale green, aphanitic to fine grained, weakly foliated, altered volcanic ash or tuff, moderate veinlet density. Shattered, broken core, poor recovery	P N	VU	Ap	1	IARG	P	4											4	G	1
10	20.7	As above without oxidized fractures. Shattered, rubbly core, poor recovery. Minor anhydrite on fractures, dissolution maybe cause of rubble nature.	P N	VU	Ap	1	IARG	P	4											5		
20.7	24.5	As above, but with good competency and recovery. Veins are mostly parallel to sub-parallel to foliation. Abundant dissem py and veinlets of clustered pyrite parallel and sub-parallel to CA	P N	VALT	Ap	1	IARG	P	4				60							5		
24.5	36.4	As from 10-20.7 Rubble zone?	P N	VALT	Ap	1	IARG	P	4											5		
36.4	53.2	As from 20.7-24.5. 1cm anhydrite veinlets at 49.8, 50.3	P N	VALT	Fo	1	IARG	P	4											5		
53.2	54.65	Fault zone, clayey gouge layers and sheared, foliated, bleached rock, qtz veins are crushed	W G	FLTZ	Fo	3	QSP	P	5				55	fl						5		
54.65	72.5	Schistose, foliated, bleached, altered volcanic tuff? Int. QSP and remnant IARG?, abundant dissem, veinlet, and irregular coarse clusters of pyrite, very few qtz veinlets, minor dissem mo>cpy	P G	VALT	Fo	3	QSP	P	5	IARG	P	1	55							5		
72.5	73	fault zone		FLTZ									55	fl						5		
73	85.5	as from 54.65-72.5	P G	VALT	Fo	3	QSP	P	4	IARG	P	1								5		
85.5	85.6	fault zone - several mm to cm gouge lined shears parallel to foliation		FLTZ									50	fl						5		
85.6	98.75	as from 54.65-85.4 Homogeneous lith and altn, few veinlets. Schistose	P G	VALT	Fo	3	QSP	P	5	IARG	P	1								5		
98.75	99.58	fault zone with soft, sheared intervals, mm to 2cm thick, oblique and parallel to fol'n, cm scale, milky white qtz-chl veins		FLTZ										fl						5		
99.58	126.1	Homogeneous textured, altered, schistose volcanic tuff, few veinlets. More int. QSP alteration in haloes around py/qtz veinlets and pyritic intervals. Mafic fragments are more heavily pyritized	P N	VALT	Fo	3	IARG	P	4	QSP	P	1	55							5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
126.1	129.8	shear zone, several mm to cm scale white clayey gouge intervals and milky white qtz-chl veins up to 7cm thick, bleached QSP altered host rock. Gouge layers at 126.75, 127.3, 127.6, 128.3, 128.75 parallel to fol'n	P G N	VALT	Fo	4	QSP	P	3	IARG	P	1	55	fl						5		
129.8	148.1	As from 99.58-126.1 but texture is more speckled due to remant chl-py replaced mafic fragments/crystals where sericitization is not total. Also a few scattered mm/cm scale cal-anhyd vnlts (anhydrite cored). Less pyritic.	P N	VALT			IARG	P	4	QSP	P	1	50							5		
148.1	148.5	Sheared, bleached zone, gouge layers parallel to fol'n	P G	FLTZ			QSP	P	5					fl						5		
148.5	151.5	as from 129.8-148.1	P N	VALT			IARG	P	4	QSP	P	2								5		
151.5	153.2	Sheared, bleached as from 148.1-148.75	P N G	VALT			QSP	P	5	IARG	P	2	50							5		
153.2	157.9	spotted to blotchy texture, vaguely porphyritic, may reflect original texture or hornfels texture? Qtz veining with cpy increasing with depth	P N	VALT	Mo	2	IARG	P	3	QSP	P	2								5		
157.9	160.7	As above, but int. crackled with submm to mm scale white gypsum, however rock is competent	P N	VALT	Mo	2	IARG	P	3	QSP	P	3	55							5		
160.7	181.5	fol'd to mottled texture, reflects increasing IARG overprint, scattered cm scale, late, ragged milky white qtz veinlets, and weak stockwork of grey, crackled qtz vnlts with py-cpy. Note coarse aggregate of cpy, 1cm, at 167.8	P N	VALT	Mo	2	CL	P	3	IARG	P	3	55							5		
181.5	183.1	sheared QSP altered, veined zone, pyrite rick	P G	VU			QSP	P	5											5		
183.1	213	Distinctive diffuse mottled and speckled texture, like altered porphyry, but may be hornfelsic alteration. Mt-py rich, cpy increasing with depth.	N K	VALT			CL2	P	3	IARG	P	2								5		
213	214.7	int. veined zone, 40% qtz, 1% cpy	N	QTVN			QSP	P	5											5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
214.7	255.6	As from 183.1-213, somewhat less mt, more patchy IARG bleaching, variable texture. Mafics more heavily chl-py altered. Mostly massive, unfol'd except in IARG altered intervals. Note angular fine grained zenoliths of sedimentary or volcanic rock at 243.4, 254.8Low veinlet density. Scattered late qtz-cal-chl and cal veinlets, 2cm thick, anhydrite lined fractures, rare veinlets.	N G	VALT			CL2	P	3	IARG	P	2								5		
255.6	266.4	typical VALT texture, mm scale, waxy dark green chl'd mafic fragments generally aligned with foliation in finer, paler matrix.	D N	VALT	Fo		CL	P	2	IARG	P	3								5		
266.4	266.5	Shear/fault zone. Soft clayey gouge and crushed rock at 65d to CA.	G	FLTZ			QSP	P	4											5		
266.5	267.8	As from 255.6-266.4	D N	VU			CL	P	2	IARG	P	3								5		
267.8	267.9	fault zone with mylonitic texture (annealed)	G N	FLTZ			CL	P	2											5		
267.9	268.2	coarse qtz-cal-chl vein	W	QTVN																5		
268.2	269	transition zone with some shearing, coarse QCC veins, broken up qtz veinlets	G N	VU			CL	P	4											5		
269	277.3	variably sheared stockwork veining and blotchy late QCC veins	G N	VALT			CL2	P	4	QSP	V	1								5		
277.3	300	well veined, textured obliterated by alteration	G	VALT	Ms		CL2	P	3	QSP	V	2								5		
300	300.9	massive coarse QCC vein	W	QTVN			CL	P	4											5		
300.9	365.1	well veined and mineralized rock. Mostly CL2 (chl-mt) with QSP overprint in haloes surrounding thicker veins. A few late mm/cm scale py veinlets. Coarse cpy blebs in late QCC veinlets.	D N	VALT	Ms		CL2	P	4	QSP	V	2								5		
365.1	365.5	mafic dyke, late and unaltered, unveined. Weak flow banding parallel to contacts at 45d to CA	D N	DDRT																5		
365.5	414.9	As from 300.9-365.1, thicker veins (5-15cm) have wide haloes of bleached QSP alteration and assoc. late py.	N	VALT			CL2	P	3	QSP	V	2								5		
414.9	417	As above, QSP, fol'n parallel veinlets dominant	P N	VALT	Fo	3	QSP	P	4	CL	P	2								5		
417	433	As above, with CL2>QSP except for isolated meter scale intervals around thicker veins	N	VALT	Fo	1	CL2	P	3	QSP	V	2								5		
433	460	As above. Qtz veinlets have mm scale calcite filled crackles perpendicular to vein edges	N	VALT	Fo	1	CL2	P	3	QSP	V	3								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
460	465	As above with QSP dominant, moly more abundant.	P N	VALT	Fo	2	QSP	P	4	CL2	P	1								5		
465	477.3	Vein density decreasing with depth. Mt in ragged patches, veinlets, and in qtz veinlets.	N	VALT	Fo	1	CL2	P	4	QSP	V	1								5		
477.3	501.5	Similar to above	P N	VALT	Fo	1	CL2	P	3	QSP	V	2								5		
501.5	504	heavily veined QSP altered interval, some shearing	P N	VALT	Fo	1	QSP	P	4	CL2	P	1								5		
504	504.5	fol'd py-chl rich rock, sheared, maybe fluidized breccia?	N K	VALT	Fo	3	CL	P	4											5		
504.5	518.7	fine fragmental tuff, with typical VALT texture, lineated ragged dark waxy green, mm scale fragments in paler, fine grained matrix. Texture obliterated in stronger QSP altered intervals. Mostly fol'n parallel stockwork veinlets. Suttle alteration transitions	N	VALT	Fo	2	CL2	P	4	QSP	V	2								5		
518.7	542.7	similar to above, but QSP altered intervals increasing in intensity and abundance very gradually. Mt rarer than above, Mo more common, as well as py only veinlets	P N	VALT	Fo	2	CL2	P	3	QSP	V	3	45							5		
542.7	543.3	fol'd black biotite-chl-py altered interval, with a few similar 2-5cm thick intervals in surrounding rocks as well	K	VALT	Fo	3	CL2	P	4											5		
543.3	609.2	aphanitic to fine grained andesitic tuff, massive to mod. Fol'd, QSP altered intervals focused on thicker veins, suttle alteration transitions. Stockwork veining decreasing with depth, Mo increasing. Fol'n angles vary from 40 to 45d to CA. One cm fault gouge, 45d to CA parallel to fol'n at 544.9m, and at 569.2m 40d to CA with 20cm QSP halo. Scattered cm scale late QCC veins, minor calcite filled crackles esp. in qtz stockwork veins.	D N	VATF	Ap	1	QSP	V	3	CL2	P	2	40							5		
609.2	624.7	crystal tuff, 1-2mm xls, variably altered to chloite or sericite. Very weak magnetite, weak carbonate and later calcite veins, some with blebs of chalcopyrite. Pyrite mod-stg. CL2 and QSP/IARG about equal in strength. Stockwork qtz vning is weaker, veins commonly .2mm to 1cm with few >10cm. veins and foliation run 50 to 60 deg to CA, mostly about 55deg.	A N	VAXT	Ck	2	CL2	P	3	IARG	P	2	55	stv	12	55				5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
624.7	650.7	ash tuff, fine to aphanitic groundmass. Moderate to strong IARG locally QSP, with weak chlorite. Pyrite seems to increase slightly from previous interval, chalco is weaker, moly increases slightly. Qtz vein density is slightly less, with a few more thick veins (20-35cm). No indication of magnetite, reduced calcite. qtz vein angle and foliation vary from 50-70deg most around 60deg. EOH due to slow drilling.	A N G	VATF	Ck	1	IARG	P	4	CL	P	1	60	stv	10	60				5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	2.25	Casing/Overburden		OVBD																		
2.25	11	Typical tuffs, w/ some 1-3mm lapilli, in ash matrix. Dominately CL2 alteration with mag and weak carbonate. Moderate qtz vning, wk py, cp, tr moly. Weak oxides, mostly in fractures, locally strong bleeding out of fracts into wall rock.	D N	VALT			CL2	P	4				40	stv	20	50				4	L,H	1
11	11.9	NREC		NREC																		
11.9	23.85	Typical tuffs, w/ some 1-3mm lapilli, in ash matrix. Dominately CL2 alteration with mag and weak carbonate. Moderate qtz vning, wk py, cp, tr moly. Weak oxides, mostly in fractures, locally strong bleeding out of fracts into wall rock.	D N	VALT			CL2	P	4				40	stv	20	50				4	L,H	1
23.85	24.45	NREC		NREC																		
24.45	49.6	Typical tuffs, w/ some 1-3mm lapilli, in ash matrix. Dominately CL2 alteration with mag and weak carbonate. Moderate qtz vning, wk py, cp, tr moly. Weak oxides, mostly in fractures, locally strong bleeding out of fracts into wall rock.	D N	VALT			CL2	P	4				40	stv	20	50				4	L,H	1
49.6	52.55	DDRT, chloritized	D N	DDRT			CL	P	5											5		
52.55	58.7	LOST CORE, box dropped during shippment due to improper rigging. Remainder sampled but don't use for resource calculations.		NREC																		
58.7	92	VALT, (possible biotite porphoroblasts) mod CL2, variable magnetite <1% to 5%, patches of v wk KP. Mod stockwork veining continues with vns ranging in width from .1cm to 20cm average is <1cm. Wk variable pyrite, <.5 to 3%, .2-.5 cp and traces of moly.	N	VALT	Wm	1	CL2	P	4	KP	Pch	1	45	stv	20	55				5		
92	106.3	Typical tuffs, moderate CL2 with weak pervasive KP, slight increase in Mag and pyrite, increase in cp with more clots. Several late qtz/chl vns some with cp, ofter these veins are perpendicular to earlier veining.	N	VALT	Ck	2	CL2	P	3	KP	P	1	50	stv	10	50				5		
106.3	115.8	VALT, CL2 2 or 3 vein sets plus late qtz/chl and late siderite vning.	N	VALT	Ck	2	CL2	P	4				50	stv	15	60	vn	2	70	5		
115.8	116	Fault zone, moderate clays, increased sulfides, qtz vning and calcite	A N	FLTZ	Ck	3	IARG	P	5	CL	P	2	55							5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
116	131.2	VALT, CL2 2 or 3 vein sets plus late qtz/chl and late siderite vning.	N	VALT	Ck	2	CL2	P	4				50	stv	15	60	vn	2	70	5		
131.2	160.1	VALT (biotite phorphorblasts?) moderate CL2, w/ weak pervasive KP. Qtz vning weakening, few more larger vns (4-30cm), plus late qtz/chl vns (decrease to 1 every 2-3 meters as opposed to above). Slight increase in sulfides, py>cp. Fault at 141m	N	VALT	Fo	2	CL2	P	3	KP	P	1	50	vn	8	55				5		
160.1	169.6	VALT, increased CL2 alt. slight increase in calcite, more erratic qtz vning. Foliation is stronger. 184.15 - 185.7 carbonate vein.	D N	VALT	Fo	3	CL2	P	4				60	vn	7	50				5		
169.6	170.1	NREC																				
170.1	189.3	As before NREC	D N	VALT	Fo	3	CL2	P	4				60	vn	7	50				5		
189.3	204.9	VALT CL2 about same but with wk perv KP. Slight increase in qtz veining and disseminated cp. Reduction in calcite vning, but still some 1-6cm white/pink veins +- chlorite.	D N	VALT	Ck	1	CL2	P	4	KP	P	2	55	vn	9	60				5		
204.9	222.4	VALT, coarser apparent texture almost porphyritic, speckled. Mod CL2, mag etc, increase in calcite again. Some weak IARG, possibly causing speckled appearance or may be crsytal tuff.	D N	VALT	Fo	3	CL2	P	4	IARG	P	2	60	vn	15	60				5		
222.4	248	VALT, moderate CL2 w/ patchy IARG. Qtz veining consists of a few larger (5-20cm) vns and a few smaller (1mm-1cm). Pyrite is very weak mostly <1%, cp .3-.7%. Calcite and magnetite with traces of KP	N	VALT			CL2	P	4	IARG	Pch	2	50	vn	5	60				5		
248	248.7	DDRT, chloritized	D N	DDRT			CL	P	3											5		
248.7	249.5	As before Dike	N	VALT			CL2	P	4	IARG	Pch	2	50	vn	5	60				5		
249.5	251	DDRT, chloritized	D N	DDRT			CL	P	3											5		
251	268	Typical tuff, CL2 alt, w wk perv KP and traces of IARG. Magnetite and qtz vning weakening some, some reddish carbonate veins. Sulfides weakening slightly	D N	VALT			CL2	P	4	KP	P	1	55							5		
268	269.4	VAXT, w/ Propylitic alteration, Epidote increasing slightly with depth as are mag and calcite. Weak structure at start of interval, ground a bit blocky.	N	VAXT	Ck	1	PR	P	3											5		
269.4	270.6	NREC																				

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
270.6	286	VAXT Propylitic with chlorite dominant and weak spotty epidote. Rock continues to be broken and somewhat blocky. Crystals in tuff appear to be k-spar. Only widely scattered qtz veins.	N	VAXT			PR	P	3	IARG	Pch	1	55							5		
276.8	277	Fault with clay, rock flour and chuncks.	A N											fl	1	55						
286	305.8	feldspar porphyry, with weak pervasive propylitic alteration, epidote is locally strong. Some chlorite, magnetite and calcite. Narrow bands of what appear to be crystal tuffs, 10-50cm wide. Qtz veining scattered, chalco and moly coarser than "usual". pyrite is weak.	A N, G	PPFP	Po	4	PR	P	2											5		
305.8	307.4	Crystal tuff, propylitic alteration with some sericite, magnetite and low sulfides.	D N	VAXT			PR	P	4				60							5		
307.4	310.3	Porphyry as above.	A N, G	PPFP	Po	4	PR	P	2											5		
310.3	314.5	VAXT with propylitic and KP alteration. Locally strong chalco. Calcite veins and late qtz/chlorite veins, very few qtz veins.	D N	VAXT	Po	1	PR	P	2	KP	P	2	60							5		
314.5	331	xl tuff with weak propylitic alteration, magnetite, epidote, calcite and weak chlorite. Some late qtz/chlorite veins. Few scattered qtz veins plus numerous calcite veins. Disseminated very weak pyrite and chalco, locally strong moly.	N	VALT			PR	P	2											5		
331	360.5	Mixed tuffs, crystal, ash and lapilli. Weak propylitic and kp alteration. Most veining is carbonates, with fewer qtz/chlorite than above and very grey qtz veins. Sulfides generally very weak, locally strong Moly, esp close to some veins. Few narrow 20 to 40 cm intervals of PPFP.	N	VALT	Po	1	PR	P	2	KP	Pch	2	65							5		
360.5	362.7	Tuff with IARG increased moly, qtz veining, pyrite and weak chlorite.	G	VALT	Fo	2	IARG	P	4	CL	P	2	45							5		
362.7	366.3	crystal tuff with traces of IARG over PR, sulfides continue to be weak. Late calcite veins, couple of qtz veins and mo + cp	A N, G	VAXT			PR	P	3	IARG	P	1	65							5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
366.3	386.9	Feldspar porphyry with propylitic alteration, epidote, chlorite, mag+. Late qtz/chlorite veins and some anhydrite vning. Weak grey qtz veining. Dis chalco and blebs (at 370.3 bull qtz vein with blebs to 3cm x 1.5cm), plus occasional veinlets. Moly dis and in some veins and fracture surfaces.	A N, G	PPFP	Po	3	PR	P	3												5		
386.9	396.7	lapilli tuff and/or crystal tuff. Propylitic alteratin wk to mod chl>ep, magnetite and calcite. Increase qtz veining with moly, also qtz/carbonate and qtz chlorite veins (late). Slight increase in sulfides esp chalco and moly. Weak patchy IARG, no systematic vein orientation.	N	VAXT			PR	P	2	IARG	Pch	1	60								5		
396.7	399.4	PPFP, wk propylitic alteration, ep>chlor. Contacts at ~30deg to CA. Minor qtz veining. Locally strong mag. Weak sulfides, cp > py, traces of moly	A N	PPFP	Po	3	PR	P	2					vn	1	30				5		
399.4	409.1	lapilli tuff with moderate propylitic alteration, cl>ep plus mag and increased calcite. Locally strong sulfides, esp in healed shears, overall weak. Very weak qtz veining.	N	VALT			PR	P	3				60	vn	3	70				5		
409.1	421.6	PPFP, wk propylitic alteration, ep>chlor plus mag and calcite. Late qtz/chlorite veins, fewer calcite veins than interval above, a few qtz veins. Weak sulfides, touch of anhydrite veining. Possible chlorite after hornblende.	A N	PPFP	Po	4	PR	P	3					vn	2	60				5		
421.6	424.3	crystal tuff with weak propylitic alteration, very few qtz veins and generally weak sulfides. EOH.	N	VAXT			PR	P	3					vn	1	60				5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	9.75	Overburden, casing, rubble		OVBD																		
9.75	85	Grn-Dk grn, minor gry grn zones, volcanics. Mod CL alteration, locally wk magnetite w/minor carb veining. Locally 30-80cm wk QSP zones w/incr. gry crackled Qtz veining. Incr. grn ser below 55m.	G, A N	VATF	Bd	1	CL	P	3	QSP	Pch	2	55							5		
85	116.8	Mod QSP alt'd volcanics. More pervasive grey ser, w/out real distinct Qtz. Whispy "ghosty" Qtz veining w/coarse sulphides on margins. Zones w/wk CL down to 89.5m. Wk clays + 5-10cm frac zones at 89.45 and 92.6m.	G	VUTF			QSP	P	4											5		
116.8	152.8	Similar to above w/less alt'n. Locally 1-1.5m zones w/incr grn ser +/- CL. 5-10% Qtz vng. 4-5% sulphides w/locally gaudy Cpy	G, G N	VUTF			QSP	P	3	IARG	Pch	2								5		
152.8	168.1	Mod IARG w/local wk CL + patchy QSP	N G	VATF			IARG	P	2	QSP	Pch	2								5		
168.1	239	Mod-Str QSP alt'd volcanics w/10-25% Qtz, 6-10% Py as vns and clots, 0.2-0.4% Cpy, and locally Tr Moly on fracs. 10-15% Anhy from 171.3 - 174.7m w/Qtz rims common. Mixed gry clays + Qtz frags / frac. Zone @ 185.35 - 185.75m. 2cm core axis parrallel clay seam @ 233.0-233.1m	G	VUTF			QSP	P	5											5		
239	267	Mixed CL > QSP > IARG alt'n. Still just 10-25% Qtz at all orientations. CL matrix +/- Wk Mt. Locally semi-massive sulphides tp 5cm @ 45 deg. TCA	N G	VATF			CL	P	2	QSP	Pch	3								5		
267	329	Similar, w/incr. QSP zones. ~ 5m QSP dominant, then 5m CL dom. 10-40% Qtz vng. + 4-5% Py, 0.2-0.4% Cpy + locally tr Moly. Vug @307.2m w/cpy xls + Bn?	G N	VATF			QSP	Pch	4	CL	Pch	3								5		
329	410.2	CL > QSP now. Perv. C.g. chloritized volcanics w/1-2m zones of wk-mod perv. QSP alt'n. 5-12% Qtz, 3-5% Py, 0.2-0.4% Cpy assoc. w/Py vnlts + stringers	N G	VATF			CL	P	3	QSP	Pch	2								5		
410.2	411	No rec. rubble above, and regrind core		NREC																		
411	430.3	As above description. Zone split by NREC is all	N G	VATF			CL	P	3	QSP	Pch	2								5		
430.3	442.6	Wk-mod perv. QSP Alt'n. Wk patchy CL alt'n. 10-20 Qtz vns/m totalling 10-15%. Sulphides still high @ 6-7%. 442.55 = EOH	G N	VUTF			QSP	P	3	CL	Pch	2								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	6.4	Overburden and casing																				
6.4	29.55	unknown protolith, strong QSP, locally to stockwork or massive qtz vein. Patches of weak chlorite, original? Sulfides 5-12% pyrite>cp traces of moly. Few late qtz veins, milky white. In general veining is stronger in QSP rich zones and less in chloritic zones and is more erratic/wormy. some oxides in and close around some fractures.	A N, G	VU	Wm	3	QSP	P	5	CL	Pch	2	60	stv	20	60				4	J,L	1
29.55	35.65	Typical tuffs mostly ash with few lapilli. Mod-strong Chlorite alteration with patchy QSP. Reduced qtz veining, and reduced pyrite, sulfides in general(?).	A N, G	VATF	Wm	1	CL	P	3	QSP	Pch	1	60	stv	10	60				5		
35.65	41.85	QSP(STW), mod-strong sulfides, traces of moly. Weak undertones of chlorite.	G	VU	Ck	2	QSP	P	5	CL	Pch	1	60	stv	25	60				5		
41.85	54.65	Tuffs with pervasive chlorite and moderate patchy QSP. Sulfides highly variable, 4-8%, traces of oxides in fracs, no sigficant penetration. Veining increase in qsp zones and reduces in chlorite.	G N	VATF	Fo	2	CL	P	4	QSP	Pch	3	60	stv	10	60				5		
54.65	58.8	QSP mod to strong sulfides. Qtz veins increase some with depth. Ground is blocky and recovery is not great.	G	VU	Ck	2	QSP	P	5	CL	Pch	2		fl	0.5	60				4	J	1
58.8	59.9	NREC																				
59.9	81.85	QSPSTockwork, with increasing intensity over first few meters. Somewhat blocky ground. Late qtz/chlorite vns, some with clots of chalcopyrite. Few minor faults, and weak patchy chlorite.	G	VU	Ck	3	QSP STW	P	5	CL	Pch	1		stv	40					5		
81.85	82.9	DDRT choritized and 3 late qtz veins	N	DDRT			CL	P	4					vn	3	40				5		
82.9	123	QSPSTW, patches of chlorite, increased sulfides, 7-12%. At 109.5 late qtz/chl vein with large (2-3cm) clots of chalco and bornite intergrown/changing.	G	VU	Ck	3	QSP STW	P	5	CL	Pch	1								5		
123	124.9	Fault zone, rubble poor recovery, some gange all in QSPSTW	G	FLTZ	Ck	3	QSP STW	P	5											5		
124.9	125.8	NREC																				
125.8	128	Fault zone, rubble poor recovery, some gange all in QSPSTW	G	FLTZ	Ck	3	QSP STW	P	5											5		
128	150.1	QSPSTW, no chlorite but otherwise similar to above	G	VU	Ck	2	QSP STW	P	5											5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
150.1	150.9	NREC																				
150.9	209.8	QSPSTW late bull qtz with small blebs of cp, occasional vugs, with qtz crystals and chalco. Traces of chlorite in matrix. 204 - 208.5 broken ground shearing possible fault. Veins more irregular in nature.	G	VU	Wm	2	QSP STW	P	5	CL	Pch	1								5		
209.8	253	VALT, small scattered lapilli/biotite porphoro blasts. Mod-stg qtz stockwork. Chlorite dominant alteration of matrix but QSP seems most important, Strong patches with weaker zones. Veining is more wormy with some crackling. Sulfided slightly weaker than before. foliation wk, not much late qtz veining. Fault at 242.1 - 242.9 and 252.8-260m.	A N, G	VALT	Wm	3	QSP	Pch	3	CL	P	3	50	stv	30	40				5		
253	301.7	Tuffs with mod-strg chlorite, weak spotty QSP lessening with depth. Strong stockwork qtz veining, widths range from 1mm to 8cm. Disseminated sulfides and veinlets. Pyrite from 3-10%, cp from .4-1%. Moly seems to be increasing with depth. Scattered late qtz/chlorite veins.	N	VATF	Wm	3	CL	P	4	QSP	Pch	1	50	stv	25	50	stv	4	30	5		
301.7	303	Fault zone in QSP tuffs. 2 identifiable faults at about 30deg to CA.	G	FLTZ			QSP	P	4	CL	P	1	50	fl	2	30				5		
303	331	Tuff with mod-strg CL alteration, no visible QSP. Stockwork veining is decreasing with depth slightly. Sulfides also reduced. Foliation very weak, almost massive. Occasional late qtz/chl vein.	N	VATF	Wm	1	CL	P	4				50	stv	10					5		
331	342.4	Tuffs slightly coarser but variable. Chlorite dominant alteration. Abundant late calcite veining and wormy qtz. Increaseed sulfides, including veinlets of pyrite. Fracture/flt at 334.	D N	VALT	Wm	3	CL	P	4				45	stv	10					5		
342.4	347	Similar to above but with 3 diorite dikes, 50cm, 35cm and another 50cm separated by tuffs. Late calcite veining and some qtz. Sulfides reduced to 3-5%. Contacts on dikes vary from 40deg to 50deg to CA.	N	VALT	Wm	1	CL	P	4				45							5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
347	394.4	Mixed ash and lapilli (possible crystal) tuffs. Mod-strg chlorite alteration, weak mag and weak calcite. Qtz veining slowly reducing with depth, then pick up again a little below 379. Sulfides vary from 2 - >6% (locally). Fault at end of hole. E.O.H. 394.39	D N	VATF	Fo	1	CL	P	4				45	vn	8					5		

SEABRIDGE GOLD INC

KSM 2007 Drill Log

Hole ID: **M-07-49**

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	40.25	Pale - lt. grn fairly unaltered med-coarse grained volcanics. Minor qtz vng ~ 5%, sulphides weak. Abundant core axis parralel fractures w/goe +/- Jar common. Slight vuggy / weathered carb appearance. Mod yel/grn carb-qtz/carb vng.	G, A N	VATF	Mo	1	CL	P	2	QSP	P	1								4	G	1
40.25	71.3	mixed mod QSP > wk-mod CL alt'd volcanics. In/out, 5m zones of each. Wk oxides on fracs	G N	VUTF			QSP	P	3	CL	P	1								4	G	1
71.3	134.4	Same as above, unoxidized. Chloritic zones > QSP zones. Frac zone @ 92.0 - 93.0 w/wk clays. 3-8% Qtz, wk sulphides, diss. > vnlts	N G	VUTF			CL	P	2	QSP	Pch	3								5		
134.4	187.8	QSP = CHL. In/out of 3-4m zones of each. 7-15% Qtz vns/2m totalling 5-12%. 4-5% Py (diss>vnlts) +/- 2% Cpy. Core axis parrallel fracs common. Mod clays on fracs + 2-4cm seams in zone @ 147.3-149.4m.	G N	VUTF			QSP	Pch	3	CL	Pch	3								5		
187.8	233.9	CL > QSP w/patchy zones of wk-mod QSP. QSP waning below 206m	N G	VATF			CL	P	3	QSP	Pch	2								5		
233.9	251.7	Zone of Str. QSP alt'n bordering on stockwk. 5-8% sulphides, wormy gry qtz vns (4-6/m., totalling 10-30%) w/later whitish vns cross-cutting.	G	VUTF	Wo	3	QSP	P	5											5		
251.7	281.5	Back into CL Alt'n, m.g - c.g. tuffs w/5-8% Qtz vns parralel TCA. Minor 20-100cm wk QSP alt'd zones w/5-10% Qtz	N	VATF			CL	P	3	QSP	Pch	1								5		
281.5	298.1	QSP dominant section w/pchy 1m sections of CL>QSP. Sulphides increased. 5-10% Qtz, 5-6% Py, +/-0.3% Cpy	G N	VATF			QSP	P	3	CL	Pch	1								5		
298.1	341.4	CL dominant zone again. Wk alteration, bordering on prop. 3-5 qtz vns/m sub-parralel TCA and 45 deg. TCA	N	VATF			CL	P	2											5		
341.4	369.1	Mixed moderate QSP and Wk CL alt'n. Qtz vng increasing to 20-40% as wormy grey veins at all orientations	G N	VUTF			QSP	P	4	CL	Pch	1								5		
369.1	396.9	CL dominant alteration again. Qtz decreasing to 2-5%. 3-5% sulphides. EOH = 396.85	N	VATF			CL	P	3											5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	3.05	Casing - overburden		OVBD																		
3.05	40	typical intensely altered, veined QSPSTWK, 70% qtz by volume, remaining rock is intensely QSP altered volcanic? Veins are mm to 5cm scale, mostly parallel to fol'n due to strong structural deformation. Minor oxidation along fractures	G	VU	Fo	3	QSP STW	P	6											4	L	1
40	69.3	As above but without oxidation along fractures. Note coarse white qtz-chl+/-calcite (QCC) veins at 46.1-46.4 with cpy, 52.3-52.6, 54.45-54.75	G	VU	Fo	3	QSP STW	P	6				45							5		
69.3	72.2	mostly sheared, crushed qtz vein material, annealed in qsp matrix, earlier grey crackled qtz-sulphide veins cut by later white, cross-cutting thinner veinlets	G W	VU	Fo	2	QTV N	P	6											5		
72.2	73	Fault zone, several cm scale soft gouge zones and sheared qtz veins.	G W	FLTZ	Fo	4	QSP STW	P	6					fl						5		
73	77.4	As from 40-69.3	G	VU	Fo	3	QSP STW	P	6				40							5		
77.4	79	Fault zone, several mm to cm scale soft gouge zones, intense shearing.	G	FLTZ	Fo	4	QSP STW	P	6				35	fl						5		
79	103.7	int. QSPSTWK, mod-int sheared, crushed and mangled veins	G	VU	Fo	3	QSP STW	P	6											5		
103.7	105	Fault zone, crumbled core, ~80% lost, "cavity"	G	FLTZ	Fo	4	QSP STW	P	6					fl						5		
105	123.5	As from 79-103.7	G	VU	Fo	3	QSP STW	P	6				45							5		
123.5	126.2	grey to pale green, aphanitic dyke, chilled bleached margins. Looks more felsic than typical DDRT mafic dyke. Distinctive pale grey to white, mm-cm scale spheroids or amygdules. Barren, no veining. Upper contact at 50d, lower at 75d to CA	G N	VU	Ms															5		
126.2	129.5	As from 105-123.5	Y G	VU	Fo	3	QSP STW	P	6				40							5		
129.5	133.7	Sheared, deformed zone, contorted and mangled veins, matrix is dull yellow-grey waxy sericite or illite	N	VU			QSP STW	P	6											5		
133.7	134.5	Fault zone, sheared with mm-cm scale soft gouge layers, QCC vein	G N	FLTZ			QSP STW	P	6					fl						5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
134.5	138.5	As from 129.5-133.7	G Y N	VU	Fo	4	QSP STW	P	6				45							5		
138.5	143.2	As from 105-123.45	G	VU	Fo	4	QSP STW	P	6				50							5		
143.2	144.2	Shear zone, many shears, thin soft gouge layers parallel to foliation	G	FLTZ	Fo	4	QSP STW	P	6				40	fl						5		
144.2	148	As from 138.5-143.15	G	VU	Fo	4	QSP STW	P	6											5		
148	148.3	Fault zone, soft gouge and crushed rock	G	FLTZ	Fo	3	QSP STW	P	6				45	fl						5		
148.3	149.3	As from 138.5-143.15	G	VU	Fo	3	QSP STW	P	6											5		
149.3	151.3	Mafic dyke, bleached chilled contacts, core has lineated, mm scale lapilli like texture. Barren, no veining	D N	DDRT	Ms															5		
151.3	173.1	markedly less stockwork veining than above, fewer sulphides. Original pale green-blue IARG (CL) alteration present in several meter scale intervals.	P G N	VALT	Fo	3	QSP	P	3	IARG	P	2	45							5		
173.1	175.8	Shear zone, with 12 cm-3cm scale soft gouge layers, clay and crushed rock, parallel to fol'n, intervening rock is weak to moderately sheared with mangled, crushed veins	P G N	FLTZ	Fo	3	QSP	P	3	IARG	P	2	45	fl						5		
175.8	194	mod. Altered, fol'd andesitic tuff, maximum size fragments of a few mm, lower veinlet density, scattered veins up to 10cm thick, crackled with sulphides. Patchy intervals of bleached QSP altered zones associated with shearing	P N	VALT	Fo	2	IARG	P	3	QSP	Pch	2	50							5		
194	206.3	fine grained to aphanitic, massive ash tuff or sediment, variably sheared, deformed, intervals of mottle textured, chl'c hornfels alteration	P N G	VAAT			IARG	P	2	QSP	Pch	2								5		
206.3	208.3	Shear zone, schistose, broken core, soft gouge layers, drillers note reads "high torque, squeezing"	P G N	FLTZ	Fo	4	QSP	P	4					fl						5		
208.3	221.3	bleached, aphanitic, mottled to crackled texture, possible ash tuff or sediments, fol'n almost absent. Minor fault gouge layers from 214.9-215	P G	VAAT	Mo	2	QSP	P	5											5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
221.3	222.2	Shear zone, soft gouge and crush, sub parallel to CA, int. fractured silicified rock host	G	FLTZ	Bx	5	QSP	P	5					fl						5		
222.2	243.1	similar to 208.3-221.3, but with more intervals of fol'd QSP altered rock, low veinlet density, variably sheared. 2cm soft gouge at 230.1, 230.7, 237.9 at 65d to CA. Note from 233.6-237.3: sheared, foliated, heavily pyritic zone. Increasingly sheared, foliated, mylonitic, in bottom few meters.	G	VAAT			QSP	P	5	IARG	Pch	1								5		
243.1	244.8	Fault zone, 40% coarse milky white QCC veins, intervening rock is sheared, bleached, crackled, pyritic argillite	G W	FLTZ										fl						5		
244.8	249.9	laminated, pyritic argillite, variably crackled, probable biotite-py-mt hornfelsed?	K N	SARG	Bd	2	HFLS	P	4				35							5		
249.9	273.4	bleached, mottled, hornfelsed, fine volcaniclastics or argillite, spotted and mottled texture, irregular patches, clusters of coarse pyrite. A few intervals of grey, fine granular volcaniclastics? Some shearing from 267.5-270	P N G	SARG	Mo	2	HFLS	P	4	QSP	Pch	1								5		
273.4	281.4	pale, fine grained felsic ash tuff or volcaniclastic, minor vague laminations	P G	SARG	Ms	2	QSP	P	1				35							5		
281.4	285.6	variably sheared, heavily pyritic interval, 25% coarse dissem py	G K N	SARG	Ms	2	HFLS	P	4	QSP	Pch	1								5		
285.6	286	probable mylonitic shear zone , schistose	P G	FLTZ	Fo	4	QSP	P	5					fl						5		
286	300	bleached, mottled, laminated volcaniclastics or ash tuff, massive to weakly fol'd	P G	SARG	Ms	2	QSP	P	4	HFLS	Pch	1								5		
300	322.5	massive to weakly fol'd QSP altered volcaniclastics, rare qtz veinlets, scattered QCC veins	P G	VAAT	Fo	4	QSP	P	5				45							5		
322.5	342.9	variably textured, mottled to aphanitic, fol'd to massive, laminated in less altered remnants	P G	SARG	Ms	2	QSP	P	5	HFLS	Pch	1	45							5		

Hole ID: **M-07-51**

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	9.14	Overburden / casing		OVBD																		
9.14	27.5	Str ser + Qtz stockwk alt'd volcanics. 20-70% Qtz, 4-6% sulphids. Wk Goe on fracs. 60cm anhyd. Vn @ 26.9-27.5m	G N	VUTF	Ck	3	QSP	P	5	CL	Pch	1								4	G	1
27.5	28.5	No rec.		NREC																		
28.5	33.3	As above, slight decr. In Qtz percent (15-40%). Unoxidized now	G N	VUTF			QSP	P	5	CL	Pch	1								5		
33.3	114.5	Chlor altered volcanics. Abundant Qtz. Veining - 10-20/m and 10-25%. Locally semi massive sulphides @ 60% of core over 10-20cm lengths. Locally splashy Cpy clots within Qtz and QTC veins	N	VATF			CL	P	3											5		
114.5	143.6	Mixed, w/QSP > CL Alt'n., Still abundant Qtz veining w/qtz greatest in QSP zones	G N	VATF			QSP	Pch	4	CL	Pch	2								5		
143.6	146.3	Back into CL dominant section w/5-10 Qtz vns/m. Coarse grained lapilli tuff	N	VALT			CL	P	3											5		
146.3	147.4	No rec.		NREC																5		
147.4	215	As above, CL alt'd volcanics w/10-25% Qtz., 4-6% Py., 0.2-0.5% Cpy. 190-210m = Decreased CL alt'n = P 2	N	VALT			CL	P	3											5		
215	259.7	med. gr. - c.g. volcanics w/spotty hem alt'd intrusive clots, wk., pink k-spar. locally strong magnetite (218.6-218.75). Still CL dominant alt'n. No significant increase in sulphides	N	VATF			CL	P	2	KP	Pch	2								5		
259.7	266.4	Dior. Dike. F.g. chill margins, coarse grained core zone. Str. Perv. Epidote flooding @ 259.8-260.7m.	N	DDRT			PR	P	4											5		
266.4	277.9	Intrusive? Spotty KP alt'n w/k-spar phenos. Increasing QTC veining. Minor diss. Epi.	N	PPFP			KP	Pch	2	PR	Pch	2								5		

Hole ID: **M-07-51**

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
277.9	431.6	CL Alt'n, varies from Perv = 3, down to Perv. = 2 (at 317.5m - 322m) Lapilli tuff w/locally coarse 5mm clasts (F-spar?) mod. Qtz vng., wk diss. Epi @ 312-318m. Cpy increasing below 338m., Moly also as vnlts and frac. Coatings. Overall 5-12% Qtz., 0.2-0.5% Cpy with good Au potential. Wk hornfelsing textures at in vfg volcanics at 389.6-393.5m., Wk clays @ 393.5-393.8m., Magnetite @ 417.2 - 417.5m. w/mod Cpy. Wk epi below 403m. EOH = 431.57m.	N	VALT			CL	P	3	CL	Pch	2									5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	5.1	casing/overburden - some cored boulders																				
5.1	8.3	Shear/deformation zone - crushed, mangled qtz veins in annealed, mylonitic groundmass	G	FLTZ	Bx									fl						4	J	1
8.3	9.9	foliated andesitic tuff, a few mangled qtz and qtz-chl-cal (QCC) veins	N	VALT	Fo	3														4	J	1
9.9	12.1	schistose QSP altered volcanic, some shearing	G	VU	Fo	4	QSP	P	5											4	J	1
12.1	13.7	lost core, driller's note reads "void"																				
13.7	16.3	schistose, sheared QSP altered volcanic	G	VU	Fo	5	QSP	P	2				45							4	J	1
16.3	19.45	moderately sheared, deformed veinlets	G N	VU	Fo	2	QSP	P	2	IARG	P	2								4	J	1
19.45	23.8	heavily veined zone, 40% massive, coarse QCC, also thick early grey, crackled qtz-sulphide veins. Host rock is variably sheared, foliated	G N	VU																4	H	1
23.8	25.9		N W	VU	Fo	2	IARG	P	3	QSP	P	1								5		
25.9	26.6	Fault zone, annealed, int. sheared, mangled qtz veinlets, late QCC veins	G	VU	Fo									fl						5		
26.6	61	Int. veined, QSPSTWK altered rock. Veinlets are mostly parallel or subparallel to foliation, but still there are lots of cross-cutting veinlets, looks like compressed stockwork and ribbon veined zone	G W	VU	Fo	3	QSP STW	P	6											5		
61	62	Shear zone - bleached, int. foliated, soft gouge common on many foliation planes, qtz veinlets are crushed and mangled	G W	VU	Fo	3	QSP STW	P	6					fl						5		
62	94.65	Int. veined, QSPSTWK altered rock as above. Cm scale soft gouge zones parallel to foliation at 72.2, 73.75, 74.4-74.5, 76.3, 76.4, 76.5, 80.45, 88.5, 90	G W	VU	Fo	3	QSP STW	P	6				50							5		
94.65	96.05	Shear zone - several mm to cm scale soft gough layers parallel to foliation, qtz veinlets are crushed and mangled, annealed	N	VU	Fo	3	QSP STW	P	6					fl						5		
96.05	98.3	Barren mafic dyke - aphanitic, dark green, with mm scale flattened amygdules, contacts chilled	G W	DDRT	Ms															5		
98.3	141	mostly massive qtz vein, grey-white, aphanitic, with crackle filling and disseminated py, minor cp, some late milky white qtz veinlets with diffuse boundaries	G W	VU	Fo		QTV N	P	6	QSPS	P	4								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
141	169.1	gradual increase in grey ser-ill-py altered wallrock fragments or interstitial to vein material. Core is less competent, with more thin gouge layers esp. at boundaries of dcm scale late white qtz-chl veins. Texture is more deformed, chaotic. A few lenticular vugs in more siliceous intervals. Qtz is crackled with late dissem py, less cpy, trace to minor mol	G W	VU			QSP STW	P	6											5		
169.1	172.5	Shear planes, crackled zones associated with contacts of decim scale QCC veins related to competency contrasts	G W	VU			QTV N	P	6	QSPS	P	4								5		
172.5	188	semi-massive qtz and intense QSPSTWK with well crackled qtz, py, cpy, mol. Variable late deformation	G W	VU			QSP STW	P	6											5		
188	200.4	strong qtz veinlet stockwork, intensely deformed. Most veins are crackled, buckled, folded, mangled.	G	VU			QSP	P	6											5		
200.4	210.3	less veining, some deformation still present. More aphanitic yellow-green illite than grey sericite.	G N Y	VU			QSP	P	4	IARG	P	2								5		
210.3	211.8	sand, gravel filled cavity? Mostly drill cuttings from reaming		VU										fl						5		
211.8	242.6	altered sediments or volcaniclastics, aphanitic to fine grained, variably bleached, crackled and mottled texture, more hornfelsic alteration. Moderate veinlet density, weakly mineralized	P G N	VU	Mo	2	HFL S	P	3	IARG	P	2								5		
242.6	248	andesitic tuff - texture not obliterated. Patchy QSP mostly around thicker veinlets	G N	VU			IARG	P	2	QSP	Pch	2								5		
248	250.7	similar to above, stronger bleaching due to QSP alteration	G N	VU	Fo	2	QSP	P	4	IARG	Pch	2								5		
250.7	251.2	coarse qtz-chlorite-carbonate vein	W	QTVN									48							5		
251.2	256.5	most veinlets are subparallel to CA	P N	VATF	Fo	2	IARG	P	3	QSP	P	1	45							5		
256.5	293.6	massive, aphanitic, occasionally laminated sediments or volcaniclastics. Mottled, spotted hornfelsic texture	P N G	SARG	Bd	1	HFL S	P	3	QSP	P	1								5		
293.6	295	Fault zone - mylonite, gouge, sheared rocks, mangled veins	P N	FLTZ	My	4	IARG	P	3	QSP	P	1	70				fl			5		
295	298.5	Heavily veined zone, some deformation of veins	P N	SARG			IARG	P	2	QSP	P	2								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
298.5	310.6	fine tuff to ash tuff (felsic) and/or sediments. Pale, massive, aphanitic to fine grained, rare laminations. Veins are deformed, wormy, anastomizing but mostly parallel or subparallel to fol'n	P N	SARG	Ms	2	IARG	P	2	QSP	P	2	55							5		
310.6	311	possibly limestone horizon with sub mm dark clayey partings, white, fine grained, laminated, similar to thin horizon in hole 33. Second geologist thinks it is a calcite vein.	W	SEDS	Bd	1														5		
311	327.1	similar to 298.5-310.6, but with much less veining. Qtz veins have sub mm scale calcite filled tension gashes perpendicular to vein edges. Note more py only and py-cal veinlets.	P G N	SARG	Ms	2	HFLS	P	3	QSP	P	1	60							5		
327.1	327.2	Fault zone - mylonite, gouge at 75d to CA	W	FLTZ	My	5											fl			5		
327.2	378.9	increasing intensity, consistency of spotted, mottled hornfels texture with depth, more massive, less foliated. Py-cal veinlets> py-qtz. Clay gouge at 377.7m 1cm parallel to fol'n	G N	SARG	Ms	3	HFLS	P	3	IARG	P	2								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	4.6	Overburden - some cored till boulders		OVBD																		
4.6	8	Schistose, bleached, altered volcanics, broken up core	P N	VU	Fo	3	QSP	P	4											5		
8	28	fine to aphanitic, andesitic tuff, low vein density, weakly mineralized, local QSP/IARG bleached haloes around thicker qtz veins (10cm). Incompetent, shattered core	N	VATF	Fo	2	CL	P	3	QSP	Pch	2								5		
28	63	tuffaceous texture preserved, weak veining, some foliation. Incompetent, shattered core to 67.	D N	VATF			CL	P	4	QSP	Pch	1								5		
63	84.7	as above with minor epidote increasing with depth. Core is incompetent, shattered from 75.5 down.	D N	VATF			CL	P	4	PR	Pch	1								5		
84.7	87.6	bleached, heavily veined, pyritic	P N	VATF			QSP	P	4	CL	Pch	2								5		
87.6	127	andesitic tuff, increasing stockwork veinlet density, cm to decim scale, usually with py, cp, mt. Epidote fracture filling and replacing crystals, fragments. Core quality improves past 102m.	D N	VATF			PR	V	3	CL	Pch	2								5		
127	157.5	not much epidote past this point. Core is becoming more competent. Scattered films of anhydrite on late fractures.	G N	VATF	Tf	2	CL	P	3	PR	Pch	1								5		
157.5	161.8	abundant epidote filled fractures, patchy replacement. Some pinkish kspar and Mt around Mt rich qtz veinlets. Mm scale late pyrite veinlets.	D N	VATF			CL	P	3	PR	V	2								5		
161.8	201	Mt is common component of qtz stwk veinlets. Mt-kspar in haloes around some of the veinlets. Veinlets are crackled, filled with dissem py>cpy, tr. Mol. Note 10cm thick cluster of coarse py and cpy at 174.3	D N	VATF			CL2	V	3	PR	V	1								5		
201	260	as above, increasing vein density, random orientations. Cp, Mt-Ksp flooding/replacement between veinlets. Late qtz veinlets often have distinct yellow-orange carbonate	D N	VATF			CL2	P	4	QSP	Pch	1								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
260	328.3	similar to above, with CL2 alteration (mag-kspar-biot?) more abundant. Local QSP alteration around some thicker veins. Orange carbonate still present in some late qtz veinlets. Veins become more discontinuous, broken up, anastomizing. Vein contacts are often poorly defined and grade into altered wall rock. 1 cm clay gouge parallel to fol'n at 377.7 END OF NQ CORE. REDUCE TO BQ.	D N	VATF			CL2	Pch	3	CL	P	3								5		
328.3	338	as above	D N K	VATF			CL2	P	3	CL	P	2								5		
338	364.5	similar to above, but with very few late qtz-orange carbonate veinlets. Scattered late mm-cm scale micro-brecciated pyrite veinlet. Qtz vein contacts are typically diffuse in int. altered areas, maybe indicating complete equilibrium with K-altered host. Black color in wall rock due to fine biotite and magnetite. Qtz veins are up to several 10's of cm thick.	K	VATF			CL2	P	5	CL	P	1								5		
364.5	413	as above, but with patchy intense biotite-magnetite alteration	D N	VATF			CL2	Pch	3	CL	P	2								5		
413	417.6	transition to weaker biot-mt alteration without kspar	D N	VATF			CL	P	4	CL2	Pch	2										
417.6	420.3	zone of int. crushed, deformed veins, pyrite, possible hydrothermal breccia	D N	VATF			CL	P	4	CL2	Pch	2								5		
420.3	430	int. veined zone, higher py, lower cp and mt than from 364-413. Intervals with preserved fine tuffaceous texture.	D N K	VATF			CL	P	4	CL2	Pch	1								5		
430	500	transition back to strong mt-biot+/-kspar alteration. Qtz veins intergrown with alteration. In strong kspar zones, early magnetite veins have kspar selvages, cut by qtz veins. Cp in veins and altered wall rock esp. in mt rich zones. Py>cp	K	VATF			CL2	P	5	CL	Pch	1								5		
500	523	transition to slightly less CL2 alteration, vein density decreasing, higher py?	K	VATF			CL2	P	3	CL	Pch	2								5		
523	545.5	Mt-Kspar-biot noticeably less abundant- tuffaceous texture clearer. Cp dropping gradually with depth	K	VATF	Tf		CL	P	4	CL2	P	2								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
545.5	546.6	Shear zone - 10cm black mylonite layer bordered by fol'd, sheared, veined rocks - annealed rocks	K W	FLTZ																5		
546.6	570.5	as from 523-545.5 Last 5m noticeably paler, with higher py, some deformed and crushed veins with late calcite.	K N	VATF	Tf		CL	P	4	CL2	P	2								5		
570.5	572.8	Mafic dyke, flow banded at 45d to CA. Dark green, aphanitic. Mm scale calcite veinlets parallel to flow banding. Degree of shearing and deformed veinlets in adjacent rocks suggest the dyke invaded a pre-existing fault	D N	DDRT																5		
572.8	579	qtz veins are crushed and ragged due to deformation. Stronger kspar alteration than above dyke	K N	VATF	Tf		CL2	P	4	CL	P	2								5		
579	601	as from 523-545.5 Increasing kspar and mt flooding in haloes of qtz stockwork, qtz intergrown with wall rocks	K N P	VATF	Tf		CL2	P	5	CL	P	2								5		
601	618.5	similar to above, but noticeably stronger and more persistant kspar-mt-biot alteration, typical intergrown with qtz veins, intrusive like texture	K N P	VATF	Tf		CL2	Pch	5	CL	P	2								5		
618.5	618.6	probably mylonitic fault zone, bleached, schistose, QSP altered, some gouge	P N	FLTZ			QSP															
618.6	658	persistant patchy intervals of intense kspar-mt-biot alteration, as from 601-618.5. CL only altered intervals have well preserved tuffaceous texture	K N P	VATF	Tf		CL2	Pch	5	CL	P	2								5		
658	674.8	similar to above, but with scattered coarse plagioclase crystals throughout. Also late aphanitic, pink-orange veinlets or dykelets of kspar or aplite up to several cm thick cut mineralized qtz veins.	D N	VATF	Tf		CL2	Pch	5	CL	P	2								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
3.5	55.4	m.g. volcanics w/perv. Weak CL alt'n w/locally mod QSP alt'n. Surprisingly not oxidized. 8-15% Qtz, 3-6% Py, 0.2-0.5% Cpy as diss. + clots	N G	VATF			CL	P	2	QSP	Pch	3								5		
55.4	58.75	Stockwork Qtz zone w/40-60% Qtz., Cpy incr. to 0.4-0.8% Bleached chloritic matrix	G N	VUTF			QSP	P	6											5		
58.75	80.6	CL alt'n again. Perv = 3. abundant Qtz vns < 1 cm each totalling 10-15% on average. 4-8% Py, .3-.4% Cpy. Locally minor Mt stringers < 4 cm	N	VATF			CL	P	3											5		
80.6	98.2	Mixed; QSP > CL alt'n. Mod QSP zones 2-6m thick w/wk CL interspersed. Sulphides increasing to 5-6% Py regularly and .3-.4% Cpy. 10-20% Qtz. Nice zone overall	G N	VATF			QSP	P	3	CL	Pch	3								5		
98.2	111.2	CL dominant w/wk QSP increasing in last 2m. 5-15% Qtz, 5-6% Py, .3-.4% Cpy. 3-5% Flattened lapilli clasts	N	VATF			CL	P	3											5		
111.2	120	QSP zone again: Stronger than above. 15-25% Qtz. Consistantly 6% Py, 0.5% Cpy	G	VUTF			QSP	P	5											5		
120	179.4	CL dominant alt'n w/locally 1-2m zones w/wk-mod QSP. Qtz veining strong, 15-30%, 5-6% diss Py., 0.3-0.4% Cpy. M.g. volcanics w/local 1mm lapilli clasts. Wk vuggy rotted carbonate textures the last 1.5m	N G	VATF			CL	P	3	QSP	Pch	2								5		
179.4	211.9	QSP dominant w/mixed CL zones. QSP wk-mod to 187m then increases. 15-25% Qtz. 5-6% Py and 0.3-0.4% Cpy	G N	VUTF			QSP	Pch	4	CL	Pch	3								5		
211.9	225.8	Stockwork Qtz veining w/7-8% sulphides. Clays + gravel/flt gouge @ 213.8-214.2m w/no change in alt'n either side.	W G	VUTF			QSP STW	P	5											5		
225.8	239.6	Back into mixed CL > QSP	G N	VATF			CL	P	3	QSP	Pch	3								5		
239.6	276.8	QSPSTW w/10-20% Grn-gry ser matrix	G W	VUTF			QSP STW	P	5											5		
276.8	326.7	QSPSTW w/30% Dk grn/gry CL alt'd matrix. 20-80% Qtz w/Qtz strongest down to 300m. 7-8% Py. 0.4-0.6% Cpy	W K	VUTF			QSP STW	P	4	CL2	Pch	1								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
326.7	510	CL2 / Bio matrix w/patchy QSP/Qtz stockwork veining w/locally ser zones (50-100cm). Strong sulphides, 5-7% Py., 0.4-0.6% Cpy., and 15-30% Qtz overall. Wk Mt throughout. Wk local KP alt'n as clots + 50cm zones from 350-375m. Dk grn chlorite to Blk Bio > Cl matriz. Section w/c.g. lapilli w/decreasing qtz vng and ~ 1% 8-10mm sil alt'd feldspar xls @ 446-452m before matrix gets hammered again. 490-493m = KP increasing w/increased Cpy.	K G	VUTF			CL2	P	3	QSP	Pch	2										5		
510	544.3	c.g. lapilli tuff w/3-5mm bio replaced clasts aligned along wk fol'n. Qtz vns decreased. Wk QSP zone@531-533.5m. V. wk perv. Mt	N	VALT			CL	P	2	QSP	Pch	1									5		
544.3	544.9	v.f.g. dior dike	N	DDRT																	5		
544.9	576.2	Mixed c.g. lapilli w/CL = 2 alt'n w/locally 1-2m zones w/wk QSP alt'n. Qtz vng increased again. Increased fracturing w/semi core axis parallel fractures common. 10 & 5cm dike material @ 566.85 & 567.05m. Shear zone @ 554-556.2 w/40% clays @ 555.0-556.2m.	N	VALT			CL	P	2	QSP	Pch	2									5		
576.2	579.4	fine gr. Dior dike	N	DDRT																	5		
579.4	582.2	m.g-c.g andesitic tuffs w/wk sulphides, wk qtz vng + mod qtc vng	N	VATF			CL	P	2												5		
582.2	586.5	Dior dike w/wk carb vng	N	DDRT																	5		
586.5	612.3	Predom dark CL - Bio alt'd matrix w/abundant Qtz vng. Mod. Sulphides. Minor patchy QSP	N K	VATF			CL	P	3	QSP	Pch	1									5		
612.3	616.3	QSP zone w/str sulphides. fol'n with fracs are semi core axis parralel.	G	VUTF			QSP	P	4														
616.3	670.5	Back into blk-dk grn CL + Bio alt'n w/str qtz vng. Semi rubble zone @ 647.9-651m with Qtz % dropping below. EOH = 670.45m. 10/18/07	K N	VUTF			CL	P	3												5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	6.1	Overburden and casing.		OVBD																		
6.1	26	Typical tuffs, mostly ash with some lapilli. Pervasive CL2 moderate, with patchy QSP (1m or less) strong stockwork qtz veining. Veins from <1mm to >20cm ave. ~ 4mm, angle from 30-60deg ave 45. Minor oxides mostly in fractures. Sulfides variable generally 1-3%, slightly higher in QSP zones.	D N	VATF	Wm	2	CL2	P	3	QSP	Pch	2	45	stv	35	45				4	L	1
26	94.35	Same as above with no notable oxides	D N	VATF	Wm	2	CL2	P	3	QSP	Pch	2	45	stv	35	45				5		
94.35	94.45	Fault 40deg CA	N	FLTZ									40	fl	1	40				5		
94.45	101.6	Same as 26-94.35	D N	VATF	Wm	2	CL2	P	3	QSP	Pch	2	45	stv	35	45				5		
101.6	103.8	Dike	N	DDRT			CL	P	2											5		
103.8	120.6	Same as 26-94.35 with slightly wormier qtz veining	D N	VATF	Wm	3	CL2	P	3	QSP	Pch	2	45	stv	40	45				5		
120.6	121.6	NREC																				
121.6	177.7	Same as above with the addition of some late qtz/calcite veins with clots of pyrite.	D N	VATF	Wm	3	CL2	P	3	QSP	Pch	2	50	stv	40	50	vn	0.5	50	5		
177.7	178.5	NREC																				
178.5	179	same as above with 5cm fault at end of interval	D N	VATF	Wm	1	CL2	P	3	QSP	Pch	2	50	fl	1	50				5		
179	293.5	Tuffs with CL2 and weak patchy KP. Increase in late qtz/calc/chl veining most with clots of chalco. Slight reduction of qtz stockwork. Sulfides weaker, but still better than 0.5% chalco average. Foliation is weak. Lower "contact" gradational.	D N	VATF	Wm	2	CL2	P	3	KP	Pch	2	45	stv	25	45				5		
293.5	325.3	Very similar to 179-293 but with pervasive KP. Tuffs appear coarser, with more Cl after biotite porphoroblasts. Veining reducing slowly with depth. Generally weak pyrite, and varing chalco.	G N	VATF	Ck	1	CL2	P	3	KP	P	2	45	vn	5	45				5		
325.3	337.1	Tuffs with strong pervasive KP and wk pervasive PR (including epidote). Some recrystalization of matrix plus mafics and vary mod to strong magnetite, plus K-spar porphs. Weak qtz veining, weak pyrite, veinlets and dis chalco, traces of moly.	G N	VATF	Po	2	KP	P	4	PR	P	2	45	vn	5	50				5		
337.1	347.5	Tuffs with moderate CL2 and weak qtz veining. .5% to 2% pyrite, mod chalco, locally strong.	D N	VATF	Fo	1	CL2	P	4				45	vn	3	50				5		
347.5	350	Fault zone in tuffs, with IARG and strong crackled qtz veining with seams of chalco. Slight brecciation.	A N	FLTZ	Ck	3	IARG	P	3	CL	P	2	40	vn	5	40				5		

Hole ID: **M-07-55**

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
350	414.2	Tuffs with moderate propylitic alteration and weak to moderate pervasive KP. Some late stage qtz/calc veining (pink calc). Weak pyrite, mostly less than 1%, variable but weaker chalco, increasing moly with depth. End of Hole.	G N	VATF	Po	1	PR	P	3	KP	P	2	40	vn	5	45	vn	0.5	40	5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	3.05	casing																				
3.05	4.57	cored talus boulders																				
4.57	13.3	schistose, altered, bleached VATF, moderate veined. Variably deformed, chaotic sheared and crackled texture in places	P N	VATF	Fo	3	IARG	P	4	QSP	P	3	45							5		
13.3	31.9	not much change from above, except more chaoticaly deformed, mangled veinlets, some fracturing and shearing, weaker fol'n. A few wormy QCC veins to 3cm thick in lower 2m	P G N	VATF	Fo	2	IARG	P	3	QSP	P	3	45							5		
31.9	32.5	wormy QCC vein, with 0.25m lost core (driller's note reads "void")	W	QTVN																5		
32.5	40.3	similar to 13.3-31.9, qtz veinlets are mostly folded, bulked on small scale. 1-3 cm QCC veins fairly common, small patches of dark green CL alteration preserved	P G N	VATF	Fo	2	IARG	P	3	CL	Pch	2								5		
40.3	46.4	similar to above, but with more intense, chaotic shearing, mangling of veinlets. Shear fabric trends 20-40d to CA. 20cm QCC (+oligoclase?) pegmatite like vein. Qtz veinlets cut by summ mm calcite tension gashes perpendicular to vein edge.	P G N	VU	Bx		IARG	P	3	QSP	P	3								5		
46.4	61.75	better preserved intermittent intervals of CL alteration, QSP>IARG. Deformation of veinlets decreases with depth. Most are parallel to fol'n.	N G	VATF	Fo	4	CL	P	3	QSP	Pch	2								5		
61.75	64.3	intensely foliated QSP alteration	G	VU	Fo	4	QSP	P	6											5		
64.3	66.7	fol'd, chl altered volcanics, partially IARG altered, mod. Veinlet stockwork, most parallel to fol'n, others are buckled, folded, deformed.	N	VATF	Fo	4	CL	P	3	CL	P	3	45							5		
66.7	67.2	QCC-feldspar pegmatitic vein	W	QTVN																5		
67.2	69.3	increasing shearing, fol'n, QSP alteration	N	VATF			CL	P	3	QSP	Pch	2	45							5		
69.3	73.4	shear zone - int.fol'd, sheared QSP altered rocks, with 20% coarse, vuggy QCC veins	W G N	FLTZ	Fo	5	QSP	P	5					Fl						5		
73.4	94	int. veined, fol'd, altered zone. Not quite 100% QSPSTWK. Most veins parallel or subparallel to fol'n	P G	VU	Fo	5	QSP	P	5	IARG	P	1	40							5		
94	110.2	gradual transition to less fol'd, more IARG altered rocks (less QSP)	P N G	VU	Fo	4	IARG	P	4	QSP	P	3								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
110.2	122	gradual transition to more defomed stockwork veining with depth. Ragged cm veinlet of late moly at 118.9	P N G	VU	Fo	5	QSP	P	4	IARG	P	3	45							5		
122	149.8	transition to mainly QSPor QSPSTWK - strongly fol'd, veinlets appear to have been compressed to mostly subparallel to CA. Minor intervals of darker green, preserved CL alteration. Lower meter is sheared	P G	VU	Fo	5	QSP	P	5	IARG	P	1	55							5		
149.8	151.1	Fault zone - two 10 cm gouge zones, QCC veins, some int. sheared QSP	G	FLTZ			QSP	P	5											5		
151.1	154	40% massive QCC, remaining is sheared QSP	G W	QTVN			QSP	P	5											5		
154	168.8	int. alt'd, veined rocks. Int. qtz stwk to semi-massive qtz. Dissem. And crackle filling py >> cp	P G	VU	Fo	5	QSP STWK	P	6				45							5		
168.8	173.1	mostly semi-massive qtz. 1 cm gouge at 171.35	P G	QTVN																5		
173.1	183.8	as from 154-168.8	P G	VU	Fo	5	QSP STWK	P	6				45							5		
183.8	185.5	50% QCC veins in int. sheared QSP	W	QTVN																5		
185.5	186.7	as from 154-168.8	P G	VU	Fo	5	QSP STWK	P	6											5		
186.7	190.2	50% QCC and int. sheared QSP	W	QTVN																5		
190.2	193.6	sheared QSP qtz>py>ser (illite)	P G	VU	Fo	5	QSP STWK	P	6											5		
193.6	197.9	70% QCC and int. sheared QSP. Intervening QSP is sheared.	W	QTVN																5		
197.9	204	int. sheared QSP and massive qtz with crackled, dissem. Py>>cp	P G	VU	Fo	5	QSP STWK	P	6											5		
204	208	int. QSPSTWK altered, foliated rocks	P G	VU	Fo	5	QSP STWK	P	6											5		
208	235.2	transition to less veined, more schistose QSP	P G	VU	Fo	5	QSP	P	6											5		
235.2	248	transition to less veined IARG, more schistose	P G N	VU	Fo	5	QSP	P	5	IARG	P	2	50							5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
248	252	QCC veined zone (60%), intervening rocks are strongly QSP, sheared, broken	W N	QTVN																5		
252	257.5	IARG with mangled, buckled qtz veinlets, some yellow-greenish illite	P N	VU	Fo	5	IARG	P	4											5		
257.5	264.7	mafic dyke, massive, green, aphanitic, unmineralized. Contacts are chilled, bleached, pyrite filling crackle fractures	G	DDRT	Ms															5		
264.7	265.3	as from 251.95-257.5	P N	VU	Fo	4	IARG	P	4											5		
265.3	266.2	mafic dyke as above, sharp, microfaulted contacts oblique to CA	G	DDRT	Ms															5		
266.2	270.4	moderately sheared, crackled, strongly IARG alt'd rocks	P N	VU	Fo	5	IARG	P	5				45							5		
270.4	284	decreasing fol'n with depth, more mottled, spotted hfls textures. Moderate to weak veinlet density	P N	VU	Fo	2	IARG	P	4	HFLS	Pch	2								5		
284	304.3	back intense QSPSTWK, moderately sheared	P G	VU	Fo	4	QSP STWK	P	5				45							5		
304.3	305.3	shear zone - int. fol'd, schistose, minor gouge layers	P G	VU	Fo	4	QSP	P	5											5		
305.3	332.8	IARG altered volcanics with moderate to strong QSP overprint. Weak wormy stockwork qtz veining. Ubiquitous very fine dissem. Py. Vague spotted hornfels texture preserved in some intervals	P G N	VU	Fo	4	IARG	P	3	QSP	P	3								5		
332.8	337.2	Mafic dyke- aphanitic to fine grained at center. Massive, homogeneous. Wavy contacts at about 45d toCA	N	DDRT	Ms					QSP	P	3								5		
337.2	341.3	as from 305.3-332.8	P G N	VU	Fo	4	IARG	P	3	QSP	P	3								5		
341.3	344	Mafic dyke - with some late qtz-ankerite filled tension gashes up to 3cm thick	N	DDRT	Ms															5		
344	390	as from 305.3-332.8 Mod-strong QSP/IARG, weakly fol'd, schistose, ubiquitous fine dissem py, several minor shear zones. Very few qtz veins. Well crackled qtz vein with py at 376-376.3. Calcite veinlets increase in abundance with depth.	P G N	VU	Fo	4	IARG	P	2	QSP	P	3								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
390	428.3	as above, with fewer veinlets, less fol'n. More blotchy calcite+/-qtz veins than qtz veinlets.	P G	VU	Fo	1	QSP	P	3	IARG	P	1								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	3.05	Casing and/or overburden		OVBD																		
3.05	55.15	Typical tuffs, mostly aphanitic to fine grained w/ some lapilli/ biotite porphoroblasts. Moderate CL2 alteration, magnetite is weak to moderate, some calcite. Weak quartz veining, 1mm to >25cm width, ave 5-10 per meter. Weak disseminated pyrite with a few veinlets, variable chalcopyrite, locally strong, mostly weak. Minor crackling of veins, no significant deformation nor any significant oxides.	N	VATF	Ck	1	CL2	P	3				60	vn	7					5		
55.15	57.2	NREC																				
57.2	60.5	As from 3-55	N	VATF	Ck	1	CL2	P	3				60	vn	7					5		
60.5	61.2	NREC																				
61.2	74.4	As from 3-55	N	VATF	Ck	1	CL2	P	3				60	vn	7					5		
74.4	109	Propyliticlly altered tuffs. BADLY broken. Very weak sulfides, pyrite sometimes less than chalco. Less qtz veining than before. Some weak KP and hemitzation. Mag plus weak calcite/carbonates.	N	VATF	Po	1	PR	P	3	KP	Pch	2		vn	5					5		
109	250.8	Tuffs with moderate CL2 and very weak patchy KP. Quartz veining increases slowly with depth from about 8/m to 15/m, vein thickness remains about the same. Pyrite also increases slowly with depth but variable, chalco very variable but generally weak.	G N	VATF	Ck	1	CL2	P	3	KP	Pch	1	50	vn	10					5		
250.8	257.2	Diorite dike with some late calcite veining.	D N	DDRT			CL	P	3											5		
257.2	276.4	As from 109-250 with a slight increase in calcite veining.	G N	VATF	Ck	1	CL2	P	3	KP	Pch	1	40	vn	10	60				5		
276.4	361.5	Tuffs with moderate CL2, and weak patchy QSP, KP gone. Increase in quartz veining. Spotty increase in pyrite. Increase in calcite/carbonates, both as veins and fracture fillings in some stressed qtz, plus stringers.	N	VATF	Wm	1	CL2	P	3	QSP	Pch	2	50	stv	20	50				5		
361.5	379.6	Tuffs with moderate CL2 and weak pervasive (patchy) KP. Quartz veining about the same, pyrite is weaker, chalco locally strong, but generally weakening some. Strong magnetite. Some late calcite veining.	D N	VATF	Wm	1	CL2	P	3	KP	P	1		vn	8	65				5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
379.6	406.1	Tuffs with moderate CL2. Quartz veining about the same to a little weaker, calcite veining increases, plus late qtz vning increases. Some faulting from 390-392. pyrite continues to be weak chalco variable but weakening.	D N	VATF	Wm	1	CL2	P	3				50	vn	7	50	fl	0.2	50	5		
406.1	425.2	Tuffs with pervasive moderate CL2 and weak pervasive KP alteration. Qtz veining becoming very weak. Some late qtz/magnetite veins plus few qtz/carbonate veins. Pyrite very weak and chalco weakening, with a few local kicks. Some biotite porphoroblasts. EOH	G N	VATF			CL2	P	3	KP	P	2	50	vn	4	50				5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	4.5	Overburden and rubble		OVBD																		
4.5	56	Grn chloritic volcanics, highly broken - rubbly down to 51m. Wk Qtz vng. 1 or 2 patchy wk QSP zones 1-2m thick	N	VATF			CL	P	2	QSP	Pch	1								5		
56	75	Paler grn - gry w/QSP increasing w/wk CL background. Qtz vng increasing. Semi-msv Py @ 72.5 - 72.63m.	A N, G	VATF			QSP	P	2	CL	P	2								5		
75	115.7	Wk perv. CL w/wk QSP in 1-2m zones. Med. Grained And. Tuffs. 5-15% Qtz, decreasing overall. 4-5% Py, 0.3-0.4% Cpy, diss. & small clots.	N	VATF			CL	P	2	QSP	Pch	2								5		
115.7	140.6	QSP alt'n. stronger below 126m. Qtz vng not super strong	G	VATF			QSP	P	3											5		
140.6	215	QSPSTW. Str sulphides locally, up to 15%. 5-10cm py veins common from 160.5 - 210m. Semi-msv sulphides @ 161.28 - 161.48m. Massive Py w/tr Cpy, Tr Mo @ 164.45 - 164.70m. Qtz vns weaker down to 150m, then true stockwork	W G	VUTF			QSP STW	P	5											5		
215	235.6	Str QSP alt'n., Qtz vng drops off to 20%, Py decr. Also to 6%	G N	VUTF			QSP	P	4											5		
235.6	286	Cldominant alt'n w/patchy QSP. Med-pale grn to 257m., then darker grn / stronger chlorititc volcanics. Qtz vng mod-str @ 10-25%. Sulphides mod. @ 5-6%	N G	VATF			CL	P	2	QSP	Pch	3								5		
286	297	QSP dominant alt'n w/mod-str Qtz	G	VUTF			QSP	P	4											5		
297	297.7	f.g. Dior dike	N	DDRT																5		
297.7	309.5	Like 286-297m., QSP mod-str. Near stockwork Qtz, to minor veining locally	G	VUTF			QSP	P	4											5		
309.5	332.3	CL dominant again w/+/- 1m zones of mod. QSP. 15-25% Qtz overall w/abundant Qtz vns < 1cm thick at all orientations	N G	VATF			CL	P	2	QSP	Pch	3								5		
332.3	342	Wk-mod. QSP w/patchy CL alt'n	G N	VUTF			QSP	P	3	CL	Pch	1								5		
342	407.3	CL dominant again. Pale-Dk grn CL matrix w/.5-2m zones of wk patchy QSP. 2-4 cm clots of Cpy @367m., 5-7% Py., 0.4-0.6% Cpy. 10-30% Qtz w/abdt vns < 5 mm.	N G	VATF			CL	P	2	QSP	Pch	2								5		
407.3	422.5	QSP section w/abdt Qtz + sulphides. 1 m CL zone @ 414-415	G W	VUTF			QSP	P	4											5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
422.5	426	Abdt dk chloritized matrix	K N	VATF			CL	P	3											5		
426	468	QSP Stockwork zone w/70-90% Qtz with Py to 10% and minor sericitic matrix. Cpy ~ 0.5-0.8% as dissem. Mainly. Py as diss., clots, and vns to 2cm	G W	VUTF			QSP STW	P	6											5		
468	509.4	CL a bit less than QSP alt'n. Zones of 50-100cm w/dark Cloritic volcanics among larger zones w/str qtz vng and mod. QSP alt'n. Qtz vng decreased to +/- 30%. Sulphides still high. CL dominant @ 494-498.8m., then stronger QSP alt'n. Bleached zone w/str ser and wk breccia texture @ 506.9-507.4m.	G N	VATF			QSP	Pch	4	CL	Pch	3								5		
509.4	571	CL dominant once again. Qtz veining dropped off dramatically. Grn - Dk Grn. Increasing paler/bleaching below 568.3m. Slight increase in veining 519-527m. 8-10% Qtz., 4-5% sulphides.	N	VATF			CL	P	2											5		
571	584.7	Wk perv. QSP. Lt gry homogenous w/very little Qtz relatively	G	VUTF			QSP	P	2											5		
584.7	606	Wk-mod perv. CL alt'n. Pale grn to gry-grn m.g. volcanic lapilli tuff. 5-8 Qtz vns/m < 1cm generally. 5-10% total w/locally 30-60cm vns	A N	VATF			CL	P	2											5		
606	630	Wk perv. QSP w/patchy wk CL alt'n. Qtz vng increasing to 10-20%	G, A N	VATF			QSP	P	2	CL	Pch	2								5		
630	671.7	Dk grn-blackish CL +/- Bio matrix. Qtz incr. to 15-20% Med. Grained tuffs. Weird pale grn breccia matrix w/2-4mm wall rock clasts + Py clots at 648.75-649.25m. 5-15cm Qtz vns increasing below 651m. Sulphides decr. Slightly	D N	VATF			CL	P	4											5		
671.7	678.6	QSP zone w/mod-str perv. + Vn Qtz and str. Gry ser. matrix	G	VUTF			QSP	P	5											5		
678.6	720	CL dominant again w/10-15 Qtz vns/m. Overall Qtz = 10-20%. Patchy minor Ser zones. Msv Qtz vn @ 704.6 - 707.3m. 3 cm clay shear @ 678.6 followed by 1.2m of rubble. EOH = 720.00m.	N G	VATF			CL	P	3	QSP	Pch	2								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	2.5	overburden		OVBD																		
2.5	4.57	casing - looks like recovered core inside casing	N	VATF	Fo	1	CL	P	3											4	L	1
4.57	7.6	well veined, typical VATF, mod CL altered, low sulphides	N	VATF	Fo	1	CL	P	3											4	L	1
7.6	16.7	as above	N	VATF	Fo	2	CL	P	3											5	L	
16.7	22	int. veined, intermittently pyritic QSP altered	A G	VATF	Fo	3	QSP	P	4	CL	P	1								5		
22	25		N	VATF	Fo	3	CL	P	3											5		
25	32.8	intermittent QSP>CL	A G N	VATF	Fo	3	QSP	P	3	CL	P	2								5		
32.8	41.2		A G N	VATF	Fo	4	QSP	P	2	CL	P	3								5		
41.2	41.3	shear zone - mylonitic texture, at sharp change in alteration	G	FLTZ	Fo	3														5		
41.3	44.2	fol'd, green, andesitic tuff	A G N	VATF	Fo	3	CL	P	4											5		
44.2	44.6	coarse qtz-calcite-chlorite (QCC) vein, pegmatitic texture	W	QTVN			QSP	P	4											5		
44.6	69.7	variable QCC type blotchy veining. 5 cm vuggy anhydrite/qtz vein oblique to CA at 49.5 Minor anhydrite films on fractures	G N	VATF	Fo	3	QSP	Pch	3	CL	P	2								5		
69.7	72.6	intermittent strong QSP associated with thicker veins	A G	VATF	Fo	3	CL	P	4	CL	P	1								5		
72.6	75.5	as above	A N	VATF	Fo	3	QSP	P	3	QSP	P	2								5		
75.5	108.7	as above	A N G	VATF	Fo	3	CL	P	3	CL	Pch	2								5		
108.7	112.7	as above	K N	VATF	Fo	3	QSP	P	4	QSP	Pch	1								5		
112.7	122	as above	A N	VATF	Fo	3	QSP	Pch	3	CL	P	2								5		
122	127.5	intensely veined, pyritic	A N	VATF	Fo	3	QSP	P	5											5		
127.5	142.5	intermittent strong QSP associated with thicker veins	A N G	VATF	Fo	3	QSP	P	3	CL	P	2								5		
142.5	142.5	2cm fault gouge 35d to CA	A N G	FLTZ										Fl						5		
142.5	146.7	shattered core - abundant fractures at 30d to CA	A W G	VATF			QSP	P	3	CL	P	1								5		
146.7	152.3	as from 127.5-142.5	A N G	VATF	Fo	3	QSP	P	3	CL	P	1								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
152.3	155.6	late, barren, mafic dyke	N	DDRT																5		
155.6	185.2	andesitic tuff, mod.CL altered, mod. Vein density	K N	VATF	Fo	3	CL	P	3	QSP	Pch	1								5		
185.2	191.9	similar to above except with patchy pink-brown kspar alteration of matrix	D N	VATF	Fo	1	CL	P	3	KP	Pch	2								5		
191.9	194.8	qtz vein, massive, crackles filled with late py. Irregular contacts, probably mainly oblique to CA. QSP alt'n of wallrocks	A G	QTVN																5		
194.8	215.9	as from 155.6-185.2	D N	VATF	Fo	3	CL	P	3	QSP	Pch	1								5		
215.9	229.6	bleached, foliation and py increasing. Several nebulus, blebby qtz-sulphide veins up to 10cm thick	A G N	VATF	Fo	3	QSP	P	4											5		
229.6	229.7	fault - gouge and crushed qtz	A G	FLTZ										Fl						5		
229.7	234.5	as from 155.6-185.2	N	VATF	Fo	3	CL	P	3	QSP	Pch	1								5		
234.5	238.5	heavily veined zone - 50% nebulus qtz-sulphide crackled veins and later QCC veins	W	QTVN																5		
238.5	242.2	15% sheared, crushed qtz veins	N W	VATF	Fo	3	CL	P	3											5		
242.2	244.7	80% nebulus crackled qtz and QCC veins as from 234.5 238.5	W	QTVN																5		
244.7	248	zone of sheared,crushed veins, 20%	N W	VATF	Fo	3	CL	P	3	QSP	Pch	2								5		
248	250.6	as from 155.6-185.2	N	VATF	Fo	3	CL	P	3	QSP	Pch	1								5		
250.6	251.7	40% QCC veins, up to 20cm, nebulus forms. Some coarse cpy	N W	VATF																5		
251.7	256	as from 155.6-185.2	N	VATF	Fo	1	CL	P	2	QSP	P	3								5		
256	259.7	35% QCC veins, up to 20cm, nebulus forms. Some coarse cpy	N W	VATF			CL	P	3	QSP	P	1								5		
259.7	264	as from 155.6-185.2. Orange stained carbonates in some late veins	N	VATF	Fo	1	CL	P	4											5		
264	267		N	VATF	Fo	1	CL	P	2	QSP	P	2								5		
267	301	low vein density, low sulphides	N	VATF	Fo	1	CL	P	3	QSP	P	1								5		
301	313.2	as from 259.7-264	A N G	VATF	Fo	1	QSP	P	3	CL	P	1								5		
313.2	353.5	as from 259.7-264	A N G	VATF	Fo	1	QSP	P	2	CL	P	2								5		
353.5	356	as from 259.7-264	A N G	VATF	Fo	1	QSP	P	3	CL2	P	1								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
356	400	as from 259.7-264. QCC veins more abundant than qtz-sulphide veins. Minor epidote in fractures and selectively replacement of crystals, increase with depth. Weak to moderately but consistently mineralized. Minor QSP altn around some thicker veins. Note 1-3cm anastomizing QCC vein following CA from 372.7-373.4 10cm late mafic dyke at 373.4	A N G	VATF	Fo	1	CL	P	2	CL2	P	1								5		
400	431.9	transition to more polylithic/crystal tuff or volcaniclastic, fragments lineated along fol'n. Clear texture. Late mafic dyke from 404.7-405.2. Trace epidote. Weak veining and mineralization.	N	VALT	Fo	2	CL	P	2	QSP	Pch	1	50							5		
431.9	437.4	as from 259.7-264. Finer grained than above, diffuse texture	N G	VATF	Fo	1	CL	P	3	QSP	Pch	2								5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
0	1.22	Overburden, casing to 15'		OVBD																		
1.22	32.5	Altered and bleached schistose volcanic with strong foliation and pyrite. Quartz veining weka to absent. Minor chalcopyrite, trace to weak moly. 1 to 5 % ragged calcite veinlets. Only traces of oxides	A G N	VU	Fo	5	IARG	P	4	QSP	P	3	50							5		
32.5	33.2	Shear zone, broken core several 1-3cm gouge layers parallel to foliation.	A G N	FLTZ	Fo	5	IARG	P	4	QSP	P	3	50	fl	3	50				5		
33.2	41.5	as from 1-32 but pyrite is more intense.	A G N	VU	Fo	5	IARG	P	4	QSP	P	2	55							5		
41.5	42.5	shear zone, broken core several 1-5cm gouge layers parallel or sub-parallel to foliation.	A G N	VU	Fo	5	IARG	P	4	QSP	P	3	55	fl	4	55				5		
42.5	56.4	as from 33 - 41 pyrite up again with increase in pyrite veining.	A G N	VU	Fo	3	IARG	P	3	QSP	P	3	55							5		
56.4	74.15	Tuffs with slightly stronger IARG but weaker QSP (patchy and little qtz veining). Some minor faulting, 0.2 - 1cm gouge layers and broken ground. Pyrite is weaker than above, moly locally strong.	A N	VU	Fo	3	IARG	P	3	QSP	Pch	2	55	fl	0.3	70				5		
74.15	124.1	tuffs with moderate to strong QSP but weak quartz veining and some Silicification. Lots of broken ground. Sulfides disseminated and in veins, some times with qtz. Late qtz/calcite veins some with blebs of chalco, generally weak dis chalco. Some moly assoc with vns and dis. Quartz veining increasing very slightly with depth. Transition zone over last 2m, with anhydrite veining.	G	VU			QSP	P	3	SIL	Pch	3	55	fl	0.5	60				5		
124.1	142.9	Tuffs with moderate to strong CL, weak magnetite and some calcite. Transition from above unit in top 1-2m of this unit. Quartz decreases after transition zone. Sulfides drop noticably and then creep back up a bit at end of run. Interval near end contains some QSP and anhydrite veining.	D N	VATF			CL	P	4				55	vn	5	55				5		

Meters		Core Description & Comments	Color	Lithology			Alteration						Fol'n_ Ang	Structure 1			Structure 2			Oxidation		
From	To			Code	Text 1	Text1_ intens.	Alt'n1 Code	Alt1 Mod	Alt1 intens.	Alt2 Code	Alt2 Mod	Alt2 intens.		Struct1	Struct1_ dens.	Struct1_ Ang	Struct2	Struct2_ dens.	Struct2_ Ang	State	Type	Abnd.
142.9	175	Tuffs BADLY broken up over first 5m and last 10m of interval (rubble). CL2 pervasive moderate, with patchy to almost pervasive weak KP. Strong magnetite, weak qtz veining and some calcite veining. Weak disseminated pyrite, most pyrite as fracture fillings and veinlets. Dis cp and moly with some vnlets. Foliation is weak.	D N	VATF			CL2	P	3	KP	Pch	2	50	vn	3	50				5		
175	223	similar to above but CL2 is now PR with epidote showing, KP is weaker. Magnetite continues to be strong. Interval from 175-201m is all RUBBLE, 209.2-223m RUBBLE. Mineralization is weak.	D N	VATF			PR	P	3	KP	Pch	1	50	vn	3	50				5		
223	263	Tuffs with CL2, epidote gone, and weak KP. Rubble zone extends to about 234m then blocky and finally in to solid core again around 245m. Mineralization continues to be weak as is qtz veining.	N	VATF			CL2	P	2	KP	Pch	1	50	vn	3	50				5		
263	294	Tuffs with pervasive moderate CL2 perv weak (mod) KP and traces of epidote. Anhydrite veining scattered about. Increase chalco but overall a decrease in sulfides, more blotches and seams of chalco. Qtz vning same to slightly stronger. Increase in calcite and strong magnetite.	D N	VATF			CL2	P	3	KP	P	2		vn	5	50				5		
294	303	tuffs with CL2 patchy KP and fault from 299-299.4. shearing around this plus increased calcite and pyrite.	N	VATF	Fo	3	CL2	P	3	KP	Pch	1	50	vn	5	50				5		
303	334	Back to tuffs with pervasive PR, wk-moderate, and pervasive weak KP. Strong magnetite, calcite increasing. Quartz veining weak, some qtz vns with magnetite plus a few qtz/calcite. Pyrite weak, chalco variable with some coarse blebs. Epidote generally weak.	D N	VATF			PR	P	3	KP	P	2		vn	5	55				5		
334	388.6	Tuffs with weak to moderate PR (CL>Mag>Cal>ep), and patchy KP. 2-3 generations of qtz veining, calcite veining increasing with depth. Weak sulfides locally cp>py, some clots plus disseminated. EOH.	D N	VATF			PR	P	2	KP	Pch	2		vn	5							

APPENDIX 2

ASSAY TABLES

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-24E	G36001	356.8	358.8	0.67	0.36	9	3.9	0.1	34	0.1	88	AS7-5428a
M-07-24E	G36002	358.8	360.8	0.99	0.27	10	3.3	0.1	60	0.1	147	AS7-5428a
M-07-24E	G36003	360.8	362.8	0.49	0.25	11	2.7	0.1	32	0.1	142	AS7-5428a
M-07-24E	G36004	362.8	364.8	0.54	0.27	14	3	0.1	20	0.1	71	AS7-5428a
M-07-24E	G36005	364.8	366.8	0.98	0.23	10	2.4	0.1	18	0.1	46	AS7-5428a
M-07-24E	G36006	366.8	368.8	0.49	0.21	18	2.6	0.1	26	0.1	45	AS7-5428a
M-07-24E	G36007	368.8	370.8	0.52	0.30	15	6.5	25	32	10	34	AS7-5428a
M-07-24E	G36008	370.8	372.8	0.52	0.32	13	3.8	0.1	28	0.1	94	AS7-5428a
M-07-24E	G36009	372.8	374.8	0.26	0.29	11	4.1	0.1	22	0.1	89	AS7-5428a
M-07-24E	G36010	374.8	376.8	1.47	0.18	12	2.7	0.1	20	0.1	68	AS7-5428a
M-07-24E	G36011	376.8	378.8	1.13	0.19	13	3.1	0.1	24	0.1	62	AS7-5428a
M-07-24E	G36012	378.8	380.8	0.76	0.23	15	3.8	0.1	18	0.1	45	AS7-5428a
M-07-24E	G36013	380.8	382.8	1.02	0.25	9	5.3	0.1	30	5	76	AS7-5428a
M-07-24E	G36014	382.8	384.8	0.58	0.23	14	73.5	75	234	165	314	AS7-5428a
M-07-24E	G36015	384.8	386.8	0.64	0.21	11	7.2	10	22	10	38	AS7-5428a
M-07-24E	G36016	386.8	388.8	0.36	0.21	13	15.4	40	108	15	137	AS7-5428a
M-07-24E	G36017	388.8	390.8	0.26	0.28	12	4.8	5	68	0.1	142	AS7-5428a
M-07-24E	G36019	390.8	392.8	0.34	0.32	12	5.2	10	44	0.1	99	AS7-5428a
M-07-24E	G36020	392.8	394.8	0.43	0.25	13	5.7	0.1	58	0.1	154	AS7-5428a
M-07-24E	G36021	394.8	396.8	0.56	0.23	14	4.4	0.1	46	0.1	63	AS7-5428a
M-07-24E	G36022	396.8	398.8	0.81	0.21	10	13.6	55	46	10	73	AS7-5428a
M-07-24E	G36023	398.8	400.8	0.76	0.26	14	6.3	15	26	0.1	79	AS7-5428a
M-07-24E	G36024	400.8	402.8	0.90	0.24	13	9.6	0.1	46	5	220	AS7-5428a
M-07-24E	G36025	402.8	404.8	0.47	0.26	14	4.2	0.1	28	0.1	25	AS7-5428a
M-07-24E	G36026	404.8	406.8	0.50	0.25	12	3.5	0.1	16	5	26	AS7-5428a
M-07-24E	G36027	406.8	408.8	0.67	0.22	12	3.8	0.1	20	0.1	55	AS7-5428a
M-07-24E	G36028	408.8	410.8	0.52	0.18	10	8.7	45	34	10	42	AS7-5428a
M-07-24E	G36029	410.8	412.8	0.79	0.19	15	4	0.1	20	0.1	54	AS7-5428a
M-07-24E	G36030	412.8	414.8	0.75	0.23	14	3.9	10	62	5	66	AS7-5428a
M-07-24E	G36031	414.8	416.8	0.74	0.24	13	5.2	20	44	5	34	AS7-5428a
M-07-24E	G36032	416.8	418.8	1.22	0.28	13	3.5	0.1	18	0.1	52	AS7-5428a
M-07-24E	G36033	418.8	420.8	0.73	0.17	21	2.4	0.1	20	5	79	AS7-5428a
M-07-24E	G36034	420.8	422.8	0.74	0.22	17	3.3	0.1	34	0.1	35	AS7-5428a
M-07-24E	G36035	422.8	424.8	0.51	0.14	14	2.7	0.1	40	0.1	51	AS7-5428a
M-07-24E	G36036	424.8	426.8	0.76	0.21	31	4.1	10	22	0.1	87	AS7-5430a
M-07-24E	G36037	426.8	428.8	0.65	0.25	25	4.7	10	24	0.1	40	AS7-5430a
M-07-24E	G36038	428.8	430.8	0.56	0.20	32	6.5	0.1	34	0.1	40	AS7-5430a
M-07-24E	G36039	430.8	432.8	0.84	0.14	22	4.5	95	26	0.1	27	AS7-5430a
M-07-24E	G36040	432.8	434.8	0.76	0.20	18	3.6	15	28	0.1	88	AS7-5430a
M-07-24E	G36041	434.8	436.8	0.89	0.28	23	3.5	0.1	30	0.1	45	AS7-5430a
M-07-24E	G36042	436.8	438.8	0.51	0.23	22	2.6	5	32	0.1	63	AS7-5430a
M-07-24E	G36043	438.8	440.8	0.55	0.25	25	2.9	0.1	30	5	89	AS7-5430a
M-07-24E	G36044	440.8	442.8	2.41	0.66	25	6.9	0.1	42	0.1	69	AS7-5430a
M-07-24E	G36045	442.8	444.8	0.84	0.26	30	2.8	0.1	26	0.1	87	AS7-5430a
M-07-24E	G36046	444.8	446.8	0.71	0.22	63	2.1	0.1	24	0.1	73	AS7-5430a
M-07-24E	G36047	446.8	448.8	1.11	0.36	31	4.2	0.1	18	0.1	58	AS7-5430a
M-07-24E	G36048	448.8	450.8	0.91	0.30	38	3.5	5	24	0.1	64	AS7-5430a
M-07-24E	G36049	450.8	452.8	0.75	0.15	42	1.9	15	24	0.1	73	AS7-5430a
M-07-24E	G36050	452.8	454.8	0.75	0.23	32	2.6	10	24	0.1	63	AS7-5430a
M-07-24E	G36051	454.8	456.8	0.65	0.18	79	2.5	25	24	0.1	66	AS7-5430a
M-07-24E	G36052	456.8	458.8	1.32	0.53	34	5.2	0.1	24	0.1	29	AS7-5430a
M-07-24E	G36065	458.8	460.8	0.59	0.35	27	4.4	0.1	26	0.1	40	AS7-5430a
M-07-24E	G36053	460.8	462.8	0.65	0.22	78	3	5	18	0.1	57	AS7-5430a
M-07-24E	G36054	462.8	464.8	1.02	0.31	43	4.5	0.1	18	0.1	42	AS7-5430a
M-07-24E	G36055	464.8	466.8	1.55	0.22	45	5.1	35	24	0.1	71	AS7-5430a
M-07-24E	G36056	466.8	468.8	0.93	0.28	50	3.2	15	24	0.1	72	AS7-5430a
M-07-24E	G36057	468.8	470.8	0.96	0.26	42	3.9	0.1	18	0.1	36	AS7-5430a
M-07-24E	G36058	470.8	472.8	1.41	0.23	51	4.1	20	22	0.1	64	AS7-5430a
M-07-24E	G36059	472.8	474.8	0.72	0.19	27	2.7	30	36	0.1	100	AS7-5430a
M-07-24E	G36060	474.8	476.8	0.67	0.20	36	2.3	15	28	0.1	91	AS7-5430a
M-07-24E	G36061	476.8	478.8	0.69	0.21	31	2.9	0.1	24	0.1	83	AS7-5430a
M-07-24E	G36062	478.8	480.8	0.75	0.23	36	3.1	0.1	26	0.1	68	AS7-5430a
M-07-24E	G36063	480.8	482.8	0.57	0.19	34	3.2	25	20	5	83	AS7-5430a
M-07-24E	G36066	482.8	484.8	0.70	0.17	55	3.5	10	26	0.1	88	AS7-5430a
M-07-24E	G36067	484.8	486.8	0.75	0.19	21	2.4	10	26	0.1	51	AS7-5430a
M-07-24E	G36068	486.8	488.8	0.55	0.15	23	1.8	5	20	0.1	57	AS7-5430a
M-07-24E	G36069	488.8	490.8	0.91	0.22	46	2.5	20	22	0.1	39	AS7-5430a
M-07-24E	G36070	490.8	492.8	2.17	0.19	49	2.8	15	16	0.1	46	AS7-5430a
M-07-24E	G36071	492.8	494.8	0.78	0.21	26	22.8	35	90	10	142	AS7-5433a
M-07-24E	G36072	494.8	496.8	1.00	0.29	20	4.8	15	18	0.1	59	AS7-5433a
M-07-24E	G36073	496.8	498.8	0.69	0.23	32	2.7	25	18	0.1	34	AS7-5433a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-24E	G36074	498.8	500.8	0.81	0.24	34	3.1	15	20	0.1	33	AS7-5433a
M-07-24E	G36075	500.8	502.8	0.67	0.21	39	5.9	25	20	0.1	53	AS7-5433a
M-07-24E	G36076	502.8	504.8	0.74	0.37	45	7.3	35	20	0.1	46	AS7-5433a
M-07-24E	G36077	504.8	506.8	0.99	0.20	46	3.2	30	18	0.1	62	AS7-5433a
M-07-24E	G36078	506.8	508.8	1.03	0.32	61	5.8	20	26	0.1	40	AS7-5433a
M-07-24E	G36079	508.8	510.8	0.67	0.22	74	1.7	20	20	0.1	52	AS7-5433a
M-07-24E	G36080	510.8	512.8	0.88	0.26	50	1.8	15	16	0.1	52	AS7-5433a
M-07-24E	G36081	512.8	514.8	0.82	0.16	41	1.5	20	20	0.1	37	AS7-5433a
M-07-24E	G36082	514.8	516.8	1.13	0.30	70	2.5	20	16	0.1	40	AS7-5433a
M-07-24E	G36084	516.8	518.8	0.86	0.25	63	1.6	20	18	0.1	37	AS7-5433a
M-07-24E	G36085	518.8	520.8	0.82	0.27	44	1.6	20	16	0.1	45	AS7-5433a
M-07-24E	G36086	520.8	522.8	0.87	0.25	35	1.8	15	20	0.1	42	AS7-5433a
M-07-24E	G36087	522.8	524.8	1.01	0.31	53	2.9	20	18	0.1	42	AS7-5433a
M-07-24E	G36088	524.8	526.8	0.89	0.25	40	2.7	25	18	0.1	69	AS7-5433a
M-07-24E	G36090	526.8	528.8	0.71	0.21	60	7.9	65	30	10	60	AS7-5433a
M-07-24E	G36091	528.8	530.8	0.44	0.23	32	9.5	250	32	35	101	AS7-5433a
M-07-24E	G36092	530.8	532.8	0.76	0.32	28	14.4	330	32	45	133	AS7-5433a
M-07-24E	G36093	532.8	534.8	1.03	0.32	45	7	105	26	15	99	AS7-5433a
M-07-24E	G36094	534.8	536.8	0.72	0.28	47	11.3	215	34	35	87	AS7-5433a
M-07-24E	G36095	536.8	538.8	0.64	0.22	38	21.9	845	46	110	227	AS7-5433a
M-07-24E	G36096	538.8	540.8	0.54	0.16	55	3.6	70	24	10	44	AS7-5433a
M-07-24E	G36097	540.8	542.8	0.99	0.30	37	4.4	75	32	10	58	AS7-5433a
M-07-24E	G36098	542.8	544.8	0.96	0.31	25	4.7	75	40	10	37	AS7-5433a
M-07-24E	G36099	544.8	546.8	0.45	0.19	101	2.7	25	58	0.1	126	AS7-5433a
M-07-24E	G36100	546.8	548.8	0.63	0.17	57	2	25	22	0.1	68	AS7-5433a
M-07-24E	G36101	548.8	550.8	0.92	0.22	43	1.9	25	22	0.1	80	AS7-5433a
M-07-24E	G36102	550.8	552.8	0.96	0.37	84	3	25	30	0.1	80	AS7-5433a
M-07-24E	G36103	552.8	554.8	1.13	0.49	25	3.5	30	26	0.1	98	AS7-5433a
M-07-24E	G36104	554.8	556.8	0.96	0.42	27	4.7	25	26	0.1	66	AS7-5433a
M-07-24E	G36105	556.8	558.8	1.55	0.37	61	29.6	40	106	10	154	AS7-5433a
M-07-24E	G36106	558.8	560.65	0.72	0.24	57	8.6	30	26	0.1	70	AS7-5433a
M-07-24E	G36107	560.65	563	0.84	0.20	64	4.2	45	16	0.1	60	AS7-5433a
M-07-24E	G36108	563	565	1.20	0.33	38	4.8	55	32	0.1	64	AS7-5433a
M-07-24E	G36109	565	567	0.94	0.32	55	5.2	45	18	0.1	47	AS7-5433a
M-07-24E	G36110	567	569	0.98	0.20	58	3.2	50	18	0.1	52	AS7-5433a
M-07-24E	G36111	569	571	0.69	0.28	73	3.2	20	22	0.1	32	AS7-5433a
M-07-24E	G36112	571	573	1.06	0.37	27	4.2	10	26	0.1	32	AS7-5433a
M-07-24E	G36113	573	575	0.88	0.16	52	3.6	50	28	0.1	100	AS7-5433a
M-07-24E	G36114	575	577	0.99	0.38	32	5.4	30	36	0.1	55	AS7-5433a
M-07-24E	G36115	577	579	0.93	0.26	64	2.8	20	20	0.1	48	AS7-5433a
M-07-24E	G36116	579	581	0.87	0.19	53	2	20	16	0.1	37	AS7-5437a
M-07-24E	G36117	581	583	0.94	0.31	98	2.9	25	14	0.1	43	AS7-5437a
M-07-24E	G36118	583	585	1.07	0.22	72	2.7	20	16	0.1	62	AS7-5437a
M-07-24E	G36120	585	587	1.01	0.25	69	3.2	15	14	0.1	68	AS7-5437a
M-07-24E	G36121	587	589	0.74	0.20	67	2.2	15	16	0.1	70	AS7-5437a
M-07-24E	G36122	589	591	0.83	0.25	58	2.8	10	40	0.1	148	AS7-5437a
M-07-24E	G36123	591	593	1.09	0.29	85	2.8	15	16	0.1	54	AS7-5437a
M-07-24E	G36124	593	595	1.17	0.34	62	3.5	20	18	0.1	41	AS7-5437a
M-07-24E	G36125	595	597.25	0.66	0.14	103	2	25	16	0.1	42	AS7-5437a
M-07-25	G32751	9	11	0.82	0.36	8	3.4	20	38	0.1	44	AS7-5419a1
M-07-25	G32752	11	13	0.79	0.26	18	3.6	20	34	0.1	57	AS7-5419a1
M-07-25	G32753	13	15	0.60	0.16	18	2.5	20	32	0.1	83	AS7-5419a1
M-07-25	G32754	15	17	0.81	0.27	11	3.4	25	54	0.1	77	AS7-5419a1
M-07-25	G32755	17	19	0.84	0.26	20	2.9	20	30	0.1	62	AS7-5419a1
M-07-25	G32756	19	21	0.50	0.16	22	1.9	15	24	0.1	103	AS7-5419a1
M-07-25	G32757	21	23	0.79	0.22	24	2.9	15	24	0.1	73	AS7-5419a1
M-07-25	G32758	23	25	0.71	0.20	26	2.6	15	48	0.1	119	AS7-5419a1
M-07-25	G32759	25	27	0.82	0.18	28	3.1	15	92	0.1	90	AS7-5419a1
M-07-25	G32761	27	29	0.60	0.23	29	2.7	15	22	0.1	72	AS7-5419a1
M-07-25	G32762	29	31	0.66	0.26	23	2.7	15	20	0.1	57	AS7-5419a1
M-07-25	G32763	31	33	0.72	0.39	20	4.1	15	26	0.1	54	AS7-5419a1
M-07-25	G32764	33	35	0.58	0.26	23	2.9	15	24	0.1	43	AS7-5419a1
M-07-25	G32766	35	37	0.47	0.17	25	2.3	15	24	0.1	74	AS7-5419a1
M-07-25	G32767	37	39	0.66	0.20	17	2.6	15	34	0.1	77	AS7-5419a1
M-07-25	G32768	39	41	0.65	0.20	15	2.7	15	38	0.1	101	AS7-5419a1
M-07-25	G32769	41	43	0.48	0.21	13	2.5	15	26	0.1	68	AS7-5419a1
M-07-25	G32770	43	45	0.59	0.28	15	7.5	25	40	10	52	AS7-5419a1
M-07-25	G32771	45	47	0.67	0.19	16	3.6	25	28	0.1	93	AS7-5419a1
M-07-25	G32772	47	49	0.61	0.22	17	4.9	20	20	0.1	74	AS7-5419a1
M-07-25	G32773	49	51	0.90	0.33	13	7.2	25	68	5	88	AS7-5419a1
M-07-25	G32774	51	53	0.69	0.18	19	2.6	20	20	0.1	113	AS7-5419a1

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-25	G32775	53	55	0.83	0.27	6	3.3	30	34	0.1	43	AS7-5419a1
M-07-25	G32776	55	57	1.12	0.26	7	2.7	20	44	0.1	62	AS7-5419a1
M-07-25	G32777	57	59	0.68	0.17	14	2.3	15	38	0.1	80	AS7-5419a1
M-07-25	G32778	59	61	0.76	0.28	12	3.7	15	58	0.1	96	AS7-5419a1
M-07-25	G32779	61	63	0.77	0.17	16	2	20	46	0.1	181	AS7-5419a1
M-07-25	G32780	63	65	0.38	0.40	6	5.9	30	104	10	396	AS7-5419a1
M-07-25	G32781	65	67	0.67	0.55	8	14.6	25	102	5	319	AS7-5419a1
M-07-25	G32782	67	69	0.64	0.20	15	2.5	25	30	0.1	112	AS7-5419a1
M-07-25	G32783	69	71	0.43	0.36	13	3.7	15	38	0.1	182	AS7-5419a1
M-07-25	G32784	71	73	0.79	0.21	10	2.4	15	24	0.1	83	AS7-5419a1
M-07-25	G32785	73	75	0.46	0.19	9	2.3	15	38	0.1	76	AS7-5419a1
M-07-25	G32786	75	77	0.45	0.20	17	2.1	0.1	46	5	99	AS7-5418a
M-07-25	G32787	77	79	0.24	0.35	10	3.2	0.1	20	0.1	57	AS7-5418a
M-07-25	G32788	79	81	0.20	0.45	8	3.6	0.1	28	0.1	21	AS7-5418a
M-07-25	G32789	81	83	0.21	0.18	13	2.4	0.1	48	0.1	69	AS7-5418a
M-07-25	G32790	83	85	0.27	0.24	13	2.3	0.1	40	0.1	88	AS7-5418a
M-07-25	G32791	85	87	0.29	0.32	10	2.9	0.1	40	0.1	74	AS7-5418a
M-07-25	G32792	87	89	0.40	0.28	16	2.3	0.1	26	0.1	43	AS7-5418a
M-07-25	G32793	89	91	0.75	0.25	19	2.5	15	22	10	71	AS7-5418a
M-07-25	G32794	91	93	0.62	0.29	11	2.2	0.1	20	0.1	27	AS7-5418a
M-07-25	G32795	93	95	0.21	0.17	13	2.3	40	52	15	183	AS7-5418a
M-07-25	G32796	95	97	0.55	0.23	16	2	0.1	32	30	43	AS7-5418a
M-07-25	G32797	97	99	0.80	0.30	27	2.5	15	30	0.1	72	AS7-5418a
M-07-25	G32798	99	101	0.71	0.26	10	2.3	0.1	22	0.1	67	AS7-5418a
M-07-25	G32799	101	103	0.90	0.26	14	2.7	0.1	24	10	53	AS7-5418a
M-07-25	G32801	103	105	0.70	0.33	12	3.2	0.1	30	0.1	43	AS7-5418a
M-07-25	G32802	105	107	0.73	0.38	10	3.4	0.1	36	0.1	30	AS7-5418a
M-07-25	G32803	107	109	0.73	0.23	12	3	10	22	0.1	78	AS7-5418a
M-07-25	G32804	109	111	0.56	0.27	10	2.6	0.1	32	0.1	68	AS7-5418a
M-07-25	G32805	111	113	0.62	0.26	10	2.9	0.1	64	0.1	109	AS7-5418a
M-07-25	G32806	113	115	0.73	0.31	10	6.3	30	68	10	105	AS7-5418a
M-07-25	G32808	115	117	0.86	0.33	8	5.2	30	86	0.1	213	AS7-5418a
M-07-25	G32809	117	119	0.89	0.36	7	3.6	0.1	38	0.1	117	AS7-5418a
M-07-25	G32810	119	121	0.63	0.36	11	4.2	5	34	15	97	AS7-5418a
M-07-25	G32811	121	123	0.61	0.27	14	3	0.1	36	0.1	42	AS7-5418a
M-07-25	G32812	123	125	0.77	0.28	14	2.8	0.1	22	0.1	28	AS7-5418a
M-07-25	G32813	125	127	0.91	0.36	11	3	0.1	26	0.1	39	AS7-5418a
M-07-25	G32814	127	129	0.54	0.31	12	2.7	0.1	36	0.1	38	AS7-5418a
M-07-25	G32815	129	131	0.55	0.26	20	3.1	20	28	15	51	AS7-5418a
M-07-25	G32816	131	133	0.54	0.22	15	1.7	0.1	22	0.1	23	AS7-5418a
M-07-25	G32817	133	135	0.77	0.26	13	2.2	10	18	0.1	56	AS7-5418a
M-07-25	G32818	135	137	1.07	0.34	14	3.4	0.1	26	10	20	AS7-5418a
M-07-25	G32819	137	139	0.78	0.26	12	2.7	0.1	18	0.1	15	AS7-5418a
M-07-25	G32820	139	141	0.77	0.35	9	5	0.1	28	0.1	16	AS7-5418a
M-07-25	G32821	141	143	0.54	0.34	10	3.1	0.1	42	0.1	9	AS7-5423a
M-07-25	G32822	143	145	1.05	0.29	12	2.7	0.1	16	0.1	55	AS7-5423a
M-07-25	G32824	145	147	1.06	0.27	14	2.5	5	24	0.1	81	AS7-5423a
M-07-25	G32826	147	149	1.06	0.29	11	3.3	0.1	32	0.1	15	AS7-5423a
M-07-25	G32827	149	151	0.77	0.27	14	2.8	5	44	0.1	36	AS7-5423a
M-07-25	G32828	151	153	0.74	0.25	12	2.9	0.1	48	10	38	AS7-5423a
M-07-25	G32829	153	155	0.85	0.23	14	2.9	45	18	0.1	34	AS7-5423a
M-07-25	G32830	155	157	0.87	0.26	15	3.4	5	28	5	67	AS7-5423a
M-07-25	G32831	157	159	1.06	0.22	15	2.3	15	32	10	51	AS7-5423a
M-07-25	G32832	159	161	1.08	0.32	10	3.7	25	36	0.1	35	AS7-5423a
M-07-25	G32833	161	163	0.83	0.33	9	4.5	0.1	52	0.1	106	AS7-5423a
M-07-25	G32834	163	165	0.73	0.41	10	48.1	135	202	325	238	AS7-5423a
M-07-25	G32835	165	167	0.62	0.25	10	18.6	75	66	135	112	AS7-5423a
M-07-25	G32836	167	169	1.07	0.32	12	25.1	35	124	65	182	AS7-5423a
M-07-25	G32837	169	171	1.15	0.42	11	6.4	0.1	32	0.1	31	AS7-5423a
M-07-25	G32838	171	173	1.07	0.27	16	5.1	5	60	0.1	64	AS7-5423a
M-07-25	G32839	173	175	1.38	0.34	11	5	0.1	32	0.1	40	AS7-5423a
M-07-25	G32840	175	177	4.40	0.28	12	10.9	55	122	20	165	AS7-5423a
M-07-25	G32842	177	179	1.64	0.42	11	5.3	35	50	0.1	47	AS7-5423a
M-07-25	G32843	179	181	2.80	0.31	10	3.9	15	26	0.1	42	AS7-5423a
M-07-25	G32844	181	183	3.10	0.31	10	9.4	60	52	0.1	144	AS7-5423a
M-07-25	G32845	183	185	1.04	0.23	9	3	30	38	5	64	AS7-5423a
M-07-25	G32846	185	187	1.16	0.30	10	3	15	32	0.1	50	AS7-5423a
M-07-25	G32847	187	189	1.07	0.39	10	4.9	0.1	132	0.1	23	AS7-5423a
M-07-25	G32848	189	191	1.35	0.24	15	3	0.1	48	0.1	49	AS7-5423a
M-07-25	G32849	191	193	1.58	0.29	15	3	20	32	20	35	AS7-5423a
M-07-25	G32850	193	195	1.00	0.22	11	2.4	10	32	0.1	38	AS7-5423a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-25	G32851	195	197	1.59	0.38	10	5.5	125	56	15	79	AS7-5423a
M-07-25	G32852	197	199	1.73	0.23	12	6.9	160	58	25	164	AS7-5423a
M-07-25	G32853	199	201	0.78	0.22	11	2.8	5	80	0.1	95	AS7-5423a
M-07-25	G32854	201	203	1.18	0.32	9	3.2	5	26	0.1	27	AS7-5423a
M-07-25	G32855	203	205	1.02	0.27	10	2.9	0.1	18	5	42	AS7-5423a
M-07-25	G32856	205	207	1.79	0.49	10	6.5	20	26	10	33	AS7-5424a
M-07-25	G32857	207	209	0.81	0.36	22	3.9	0.1	44	5	60	AS7-5424a
M-07-25	G32858	209	211	1.16	0.34	12	4.1	30	36	15	36	AS7-5424a
M-07-25	G32859	211	213	0.88	0.22	15	2.8	0.1	64	5	37	AS7-5424a
M-07-25	G32860	213	215	1.06	0.22	12	2.4	0.1	26	5	28	AS7-5424a
M-07-25	G32861	215	217	1.37	0.34	13	5.4	45	50	10	72	AS7-5424a
M-07-25	G32862	217	219	0.92	0.25	12	3.3	10	30	0.1	35	AS7-5424a
M-07-25	G32863	219	221	0.93	0.40	11	5.5	60	28	15	25	AS7-5424a
M-07-25	G32864	221	223	1.06	0.25	10	2.9	50	28	0.1	31	AS7-5424a
M-07-25	G32865	223	225	1.34	0.22	12	4.3	85	34	10	37	AS7-5424a
M-07-25	G32866	225	227	1.30	0.20	11	5.6	65	34	10	65	AS7-5424a
M-07-25	G32868	227	229	0.91	0.18	13	3.3	10	22	5	48	AS7-5424a
M-07-25	G32869	229	231	1.04	0.20	17	2.8	0.1	22	20	59	AS7-5424a
M-07-25	G32870	231	233	0.78	0.17	14	2.5	10	22	10	51	AS7-5424a
M-07-25	G32871	233	235	1.36	0.31	14	3.9	0.1	22	0.1	38	AS7-5424a
M-07-25	G32872	235	237	1.30	0.23	15	3.9	10	58	0.1	29	AS7-5424a
M-07-25	G32873	237	239	0.79	0.21	17	2.7	0.1	16	0.1	12	AS7-5424a
M-07-25	G32874	239	241	1.33	0.23	14	2.6	5	28	0.1	18	AS7-5424a
M-07-25	G32875	241	243	1.47	0.32	11	4.1	20	46	0.1	133	AS7-5424a
M-07-25	G32877	243	245	1.51	0.31	11	3.6	20	44	0.1	102	AS7-5424a
M-07-25	G32878	245	247	1.60	0.30	11	3.4	50	34	0.1	47	AS7-5424a
M-07-25	G32879	247	249	1.08	0.23	8	3.1	40	30	0.1	51	AS7-5424a
M-07-25	G32880	249	251	1.83	0.25	15	2.9	25	20	15	43	AS7-5424a
M-07-25	G32881	251	253	1.21	0.26	10	3.1	25	28	0.1	42	AS7-5424a
M-07-25	G32882	253	255	0.94	0.22	10	2.8	30	30	0.1	17	AS7-5424a
M-07-25	G32883	255	257	0.88	0.31	12	4.2	25	24	0.1	34	AS7-5424a
M-07-25	G32884	257	259	1.58	0.29	14	3.9	0.1	32	0.1	58	AS7-5424a
M-07-25	G32885	259	261	1.83	0.25	16	3.8	0.1	82	5	724	AS7-5424a
M-07-25	G32886	261	263	1.13	0.33	13	4.9	0.1	84	0.1	134	AS7-5424a
M-07-25	G32887	263	265	0.86	0.26	10	2.7	0.1	92	0.1	103	AS7-5424a
M-07-25	G32888	265	267	1.37	0.18	17	1.9	0.1	40	0.1	53	AS7-5424a
M-07-25	G32889	267	269	0.92	0.17	11	1.9	0.1	18	0.1	57	AS7-5424a
M-07-25	G32890	269	271	2.84	0.31	11	3.1	0.1	38	0.1	45	AS7-5424a
M-07-25	G32891	271	273	0.73	0.28	14	2.7	0.1	56	0.1	105	AS7-5425a
M-07-25	G32892	273	275	1.17	0.28	10	2.7	0.1	26	0.1	36	AS7-5425a
M-07-25	G32893	275	277	0.21	0.37	15	3.8	0.1	50	0.1	39	AS7-5425a
M-07-25	G32894	277	279	0.47	0.44	13	4.2	0.1	102	0.1	139	AS7-5425a
M-07-25	G32895	279	281	0.68	0.36	12	5.4	0.1	56	0.1	37	AS7-5425a
M-07-25	G32896	281	283	0.74	0.21	13	2.5	0.1	64	0.1	317	AS7-5425a
M-07-25	G32898	283	285	0.51	0.22	9	2.4	0.1	38	0.1	68	AS7-5425a
M-07-25	G32899	285	287	0.65	0.16	21	2.3	0.1	36	0.1	72	AS7-5425a
M-07-25	G32900	287	289	0.90	0.15	13	1.9	0.1	26	0.1	65	AS7-5425a
M-07-25	G32901	289	291	1.42	0.24	18	3	0.1	30	20	48	AS7-5425a
M-07-25	G32902	291	293	1.43	0.49	9	4.7	0.1	20	0.1	25	AS7-5425a
M-07-25	G32903	293	295	0.61	0.15	13	1.9	0.1	188	0.1	295	AS7-5425a
M-07-25	G32904	295	297	0.87	0.17	13	1.8	0.1	38	0.1	68	AS7-5425a
M-07-25	G32905	297	299	0.28	0.31	20	4.7	0.1	236	0.1	284	AS7-5425a
M-07-25	G32906	299	301	0.59	0.29	26	5.8	50	94	45	127	AS7-5425a
M-07-25	G32907	301	303	0.31	0.39	28	3.7	0.1	66	0.1	120	AS7-5425a
M-07-25	G32908	303	305	0.69	0.34	22	3.1	0.1	26	0.1	63	AS7-5425a
M-07-25	G32909	305	307	0.63	0.15	19	1.5	0.1	14	0.1	60	AS7-5425a
M-07-25	G32910	307	309	0.84	0.37	65	3.1	0.1	40	0.1	90	AS7-5425a
M-07-25	G32911	309	311	0.66	0.21	22	1.6	0.1	22	0.1	69	AS7-5425a
M-07-25	G32912	311	313	0.88	0.35	24	3.3	10	44	5	94	AS7-5425a
M-07-25	G32913	313	315	1.47	0.39	15	3.7	0.1	38	0.1	72	AS7-5425a
M-07-25	G32914	315	317	0.33	0.21	9	2.9	10	22	0.1	54	AS7-5425a
M-07-25	G32915	317	319	0.51	0.25	19	6.1	25	34	10	51	AS7-5425a
M-07-25	G32916	319	321	0.79	0.24	13	3.6	10	18	0.1	47	AS7-5425a
M-07-25	G32917	321	323	0.63	0.25	12	4.1	35	34	0.1	38	AS7-5425a
M-07-25	G32918	323	325	0.53	0.25	14	3.2	10	28	0.1	21	AS7-5425a
M-07-25	G32919	325	327	0.41	0.15	13	2.1	5	26	0.1	64	AS7-5425a
M-07-25	G32921	327	329	0.50	0.20	14	3.1	0.1	42	10	51	AS7-5425a
M-07-25	G32922	329	331	0.38	0.16	12	2.6	15	40	0.1	95	AS7-5425a
M-07-25	G32923	331	333	0.47	0.21	16	3.3	10	70	20	98	AS7-5425a
M-07-25	G32924	333	335	0.70	0.38	33	4.9	20	44	10	45	AS7-5425a
M-07-25	G32926	335	337	0.50	0.39	15	11.8	0.1	162	0.1	353	AS7-5426a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-25	G32927	337	339	0.32	0.19	13	2.5	0.1	28	5	38	AS7-5426a
M-07-25	G32928	339	341	0.47	0.29	29	3.6	0.1	44	0.1	81	AS7-5426a
M-07-25	G32929	341	343	0.71	0.26	12	8.7	10	22	0.1	42	AS7-5426a
M-07-25	G32930	343	345	0.70	0.29	13	2.8	0.1	18	0.1	37	AS7-5426a
M-07-25	G32931	345	347	0.77	0.28	39	7.1	0.1	26	5	39	AS7-5426a
M-07-25	G32932	347	349	0.75	0.41	16	7.9	0.1	34	0.1	58	AS7-5426a
M-07-25	G32933	349	351	0.97	0.41	19	5.4	0.1	30	20	30	AS7-5426a
M-07-25	G32934	351	353	1.08	0.35	12	5.6	0.1	22	5	16	AS7-5426a
M-07-25	G32936	353	355	1.54	0.24	16	4.8	0.1	26	10	36	AS7-5426a
M-07-25	G32937	355	357	0.76	0.26	14	6.4	0.1	24	5	32	AS7-5426a
M-07-25	G32938	357	359	0.67	0.26	15	3.4	0.1	20	0.1	47	AS7-5426a
M-07-25	G32939	359	361	0.38	0.15	19	2.6	0.1	26	5	73	AS7-5426a
M-07-25	G32940	361	363	0.47	0.33	20	11.3	0.1	42	10	287	AS7-5426a
M-07-25	G32941	363	365	0.43	0.25	11	3.3	0.1	16	0.1	54	AS7-5426a
M-07-25	G32943	365	367	0.67	0.32	22	3.6	5	48	10	170	AS7-5426a
M-07-25	G32944	367	369	0.37	0.14	14	2.5	0.1	18	15	79	AS7-5426a
M-07-25	G32945	369	371	0.59	0.36	23	10.7	0.1	28	0.1	59	AS7-5426a
M-07-25	G32946	371	373	0.51	0.21	13	2.7	5	22	0.1	65	AS7-5426a
M-07-25	G32947	373	375	0.53	0.27	13	3.2	5	20	10	74	AS7-5426a
M-07-25	G32948	375	377	0.39	0.18	18	2.8	20	40	10	206	AS7-5426a
M-07-25	G32949	377	379	0.94	0.71	9	8.4	0.1	40	0.1	24	AS7-5426a
M-07-25	G32950	379	381	0.77	0.43	34	5.1	20	22	0.1	26	AS7-5426a
M-07-25	G32951	381	383	1.36	0.45	12	5.5	0.1	32	0.1	54	AS7-5426a
M-07-25	G32952	383	385	0.63	0.29	14	4.1	0.1	26	10	88	AS7-5426a
M-07-25	G32953	385	387	0.84	0.29	15	3.4	0.1	16	0.1	44	AS7-5426a
M-07-25	G32954	387	389	1.10	0.56	16	5.5	0.1	24	10	43	AS7-5426a
M-07-25	G32955	389	391	1.18	0.38	12	4.9	0.1	22	0.1	21	AS7-5426a
M-07-25	G32956	391	393	0.65	0.22	14	5.6	0.1	36	5	78	AS7-5426a
M-07-25	G32957	393	395	0.55	0.22	14	5.9	0.1	42	0.1	173	AS7-5426a
M-07-25	G32958	395	397	0.48	0.19	16	3.4	0.1	14	5	51	AS7-5426a
M-07-25	G32959	397	399	0.88	0.20	17	2.8	0.1	24	0.1	42	AS7-5426a
M-07-25	G32960	399	401	0.45	0.17	13	2.1	0.1	16	10	56	AS7-5426a
M-07-25	G32962	401	403	0.43	0.15	10	2.1	0.1	20	0.1	79	AS7-5429a
M-07-25	G32963	403	405	0.57	0.18	58	2.3	0.1	18	0.1	66	AS7-5429a
M-07-25	G32964	405	407	1.16	0.26	38	3.2	0.1	18	0.1	21	AS7-5429a
M-07-25	G32965	407	409	0.73	0.23	27	4.1	0.1	14	0.1	40	AS7-5429a
M-07-25	G32966	409	411	0.77	0.35	16	5.2	0.1	22	0.1	22	AS7-5429a
M-07-25	G32967	411	413	0.73	0.18	22	2.7	0.1	24	0.1	51	AS7-5429a
M-07-25	G32968	413	415	0.52	0.17	42	2	0.1	16	0.1	48	AS7-5429a
M-07-25	G32969	415	417	0.52	0.16	16	2	0.1	22	0.1	52	AS7-5429a
M-07-25	G32970	417	419	0.41	0.16	19	2.3	0.1	16	0.1	58	AS7-5429a
M-07-25	G32971	419	421	0.64	0.20	16	5.1	0.1	18	10	50	AS7-5429a
M-07-25	G32972	421	423	0.64	0.34	17	12.2	0.1	18	0.1	37	AS7-5429a
M-07-25	G32973	423	425	0.62	0.18	13	4.8	0.1	16	0.1	42	AS7-5429a
M-07-25	G32974	425	427	0.72	0.31	16	4.9	10	20	0.1	39	AS7-5429a
M-07-25	G32975	427	429	0.58	0.19	24	3.5	0.1	16	0.1	41	AS7-5429a
M-07-25	G32977	429	431	0.74	0.25	14	5.5	0.1	24	0.1	29	AS7-5429a
M-07-25	G32978	431	433	0.78	0.22	14	3.5	0.1	18	5	41	AS7-5429a
M-07-25	G32979	433	435	0.67	0.18	19	2.9	0.1	18	10	39	AS7-5429a
M-07-25	G32980	435	437	0.58	0.16	16	3.5	0.1	14	0.1	45	AS7-5429a
M-07-25	G32981	437	439	0.54	0.15	21	4.4	10	24	0.1	30	AS7-5429a
M-07-25	G32982	439	441	0.57	0.17	21	4.8	20	28	15	45	AS7-5429a
M-07-25	G32983	441	443	0.53	0.18	19	3.6	20	18	0.1	30	AS7-5429a
M-07-25	G32984	443	445	0.41	0.17	21	112	10	108	0.1	107	AS7-5429a
M-07-25	G32985	445	447	0.47	0.14	16	6.5	0.1	22	5	51	AS7-5429a
M-07-25	G32987	447	449	0.51	0.18	19	3.1	10	18	0.1	55	AS7-5429a
M-07-25	G32988	449	451	0.91	0.28	51	13.5	20	48	5	63	AS7-5429a
M-07-25	G32989	451	453	0.67	0.22	17	4.8	20	18	5	61	AS7-5429a
M-07-25	G32990	453	455	0.40	0.15	16	3.2	0.1	22	0.1	76	AS7-5429a
M-07-25	G32991	455	457	0.44	0.13	17	3.1	0.1	16	5	50	AS7-5429a
M-07-25	G32992	457	459	0.68	0.24	123	34.5	10	176	10	355	AS7-5429a
M-07-25	G32993	459	461	0.75	0.19	164	4.8	15	46	10	57	AS7-5429a
M-07-25	G32994	461	463	0.47	0.16	18	4.9	20	1226	0.1	54	AS7-5429a
M-07-25	G32995	463	465	0.38	0.09	11	6.2	95	178	15	75	AS7-5429a
M-07-25	G32996	465	467	0.18	0.00	0.1	0.01	30	18	0.1	80	AS7-5431a
M-07-25	G32997	467	469	0.00	0.00	0.1	0.01	35	16	0.1	79	AS7-5431a
M-07-25	G32998	469	471	0.17	0.04	22	1.8	30	22	0.1	86	AS7-5431a
M-07-25	G32999	471	473	0.55	0.27	10	3.7	20	20	0.1	64	AS7-5431a
M-07-25	G33000	473	475	0.32	0.13	16	4.3	35	16	0.1	65	AS7-5431a
M-07-25	G34101	475	477	3.20	0.17	17	19.7	40	84	0.1	86	AS7-5431a
M-07-25	G34102	477	478.6	0.32	0.19	10	21.6	180	54	40	51	AS7-5431a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-26	G34103	0	2	0.53	0.20	27	3.1	15	40	5	69	AS7-5431a
M-07-26	G34104	2	4	0.28	0.07	124	1.1	5	36	0.1	47	AS7-5431a
M-07-26	G34105	4	6	0.57	0.07	43	0.8	10	14	0.1	58	AS7-5431a
M-07-26	G34106	6	8	0.57	0.10	37	0.9	10	20	0.1	89	AS7-5431a
M-07-26	G34107	8	10	0.54	0.11	37	1.8	10	36	0.1	63	AS7-5431a
M-07-26	G34108	10	12	0.48	0.08	58	1.1	15	30	0.1	33	AS7-5431a
M-07-26	G34109	12	14	0.73	0.11	43	1	15	18	0.1	48	AS7-5431a
M-07-26	G34110	14	16	1.08	0.17	384	1.9	25	48	0.1	52	AS7-5431a
M-07-26	G34111	16	18	0.75	0.22	117	2.5	30	94	10	68	AS7-5431a
M-07-26	G34112	18	20	0.89	0.15	56	1.5	15	18	0.1	55	AS7-5431a
M-07-26	G34113	20	22	0.40	0.10	31	1.7	45	26	10	35	AS7-5431a
M-07-26	G34114	22	24	0.35	0.05	35	2.4	65	156	15	106	AS7-5431a
M-07-26	G34115	24	26	0.70	0.10	54	1.3	15	22	0.1	63	AS7-5431a
M-07-26	G34116	26	28	0.78	0.14	44	1.5	10	28	0.1	55	AS7-5431a
M-07-26	G34117	28	30	0.76	0.17	35	1.4	10	20	0.1	50	AS7-5431a
M-07-26	G34118	30	32	0.97	0.13	38	1.2	10	16	0.1	65	AS7-5431a
M-07-26	G34119	32	34	0.70	0.15	35	1.2	10	18	0.1	54	AS7-5431a
M-07-26	G34120	34	36	0.63	0.11	33	1.1	10	22	0.1	57	AS7-5431a
M-07-26	G34121	36	38	0.64	0.14	49	1.5	10	32	0.1	90	AS7-5431a
M-07-26	G34122	38	40	0.64	0.10	20	1	15	20	0.1	133	AS7-5431a
M-07-26	G34123	40	42	0.81	0.15	48	2	20	28	0.1	92	AS7-5431a
M-07-26	G34124	42	44	1.08	0.17	43	3.3	20	18	0.1	98	AS7-5431a
M-07-26	G34125	44	46	0.89	0.22	43	16.1	30	80	0.1	131	AS7-5431a
M-07-26	G34126	46	48	0.54	0.09	31	2	15	36	0.1	145	AS7-5431a
M-07-26	G34127	48	50	0.43	0.10	49	1.2	10	78	0.1	84	AS7-5431a
M-07-26	G34128	50	52	0.49	0.10	40	1.3	10	74	0.1	77	AS7-5431a
M-07-26	G34131	52	54	0.67	0.10	39	1.1	10	12	0.1	48	AS7-5432a
M-07-26	G34133	54	56	0.61	0.12	33	1	10	14	0.1	59	AS7-5432a
M-07-26	G34134	56	58	0.69	0.14	45	1.2	10	18	0.1	56	AS7-5432a
M-07-26	G34135	58	60	0.51	0.10	30	1	15	54	0.1	126	AS7-5432a
M-07-26	G34136	60	62	0.89	0.15	31	1.4	15	16	0.1	92	AS7-5432a
M-07-26	G34137	62	64	0.58	0.10	23	1	15	30	0.1	55	AS7-5432a
M-07-26	G34138	64	66	0.52	0.09	24	0.8	15	14	0.1	62	AS7-5432a
M-07-26	G34139	66	68	0.49	0.13	20	2.4	35	36	10	54	AS7-5432a
M-07-26	G34140	68	70	0.72	0.13	25	1	15	18	0.1	67	AS7-5432a
M-07-26	G34141	70	72	0.62	0.16	35	2.1	15	40	0.1	51	AS7-5432a
M-07-26	G34142	72	74	0.73	0.14	27	1.9	20	20	0.1	122	AS7-5432a
M-07-26	G34143	74	76	0.91	0.16	20	1.5	20	24	0.1	123	AS7-5432a
M-07-26	G34144	76	78	0.82	0.19	26	1.7	15	76	0.1	107	AS7-5432a
M-07-26	G34145	78	80	0.91	0.13	19	2.4	20	28	0.1	96	AS7-5432a
M-07-26	G34147	80	82	1.02	0.14	18	2	15	14	0.1	132	AS7-5432a
M-07-26	G34148	82	84	1.27	0.18	21	1.7	15	38	0.1	113	AS7-5432a
M-07-26	G34149	84	86	0.95	0.16	19	1.6	15	22	0.1	100	AS7-5432a
M-07-26	G34150	86	88	0.81	0.13	19	1.9	40	24	5	158	AS7-5432a
M-07-26	G34151	88	90	0.88	0.15	6	11.6	105	88	70	108	AS7-5432a
M-07-26	G34153	90	92	0.73	0.19	6	8.5	30	78	0.1	206	AS7-5432a
M-07-26	G34154	92	94	0.73	0.22	8	4	20	58	0.1	133	AS7-5432a
M-07-26	G34155	94	96	0.52	0.32	7	3.2	10	102	0.1	138	AS7-5432a
M-07-26	G34156	96	98	1.00	0.22	6	2.6	25	40	0.1	68	AS7-5432a
M-07-26	G34157	98	100	0.74	0.28	10	4.1	35	146	15	243	AS7-5432a
M-07-26	G34158	100	102	0.82	0.23	5	4.3	15	48	0.1	96	AS7-5432a
M-07-26	G34159	102	104	1.20	0.30	8	3.3	15	18	0.1	121	AS7-5432a
M-07-26	G34160	104	106	0.90	0.27	7	3.7	20	28	0.1	79	AS7-5432a
M-07-26	G34161	106	108	0.82	0.14	9	1.4	25	40	0.1	100	AS7-5432a
M-07-26	G34162	108	110	0.54	0.16	8	2	10	52	0.1	46	AS7-5432a
M-07-26	G34163	110	112	0.53	0.14	12	1.8	15	40	0.1	125	AS7-5432a
M-07-26	G34164	112	114	1.39	0.15	14	1.8	20	32	0.1	150	AS7-5432a
M-07-26	G34165	114	116	0.44	0.18	16	2.1	15	62	0.1	57	AS7-5432a
M-07-26	G34166	116	118	0.39	0.10	15	0.01	15	54	0.1	152	AS7-5442a
M-07-26	G34167	118	120	0.70	0.26	16	0.8	15	66	0.1	142	AS7-5442a
M-07-26	G34169	120	122	0.44	0.12	18	0.01	15	30	0.1	168	AS7-5442a
M-07-26	G34170	122	124	0.58	0.17	18	0.01	15	48	0.1	162	AS7-5442a
M-07-26	G34171	124	126	0.52	0.17	12	0.01	15	32	0.1	124	AS7-5442a
M-07-26	G34172	126	128	0.67	0.18	14	0.01	10	30	0.1	167	AS7-5442a
M-07-26	G34173	128	130	0.66	0.19	11	0.01	10	44	0.1	185	AS7-5442a
M-07-26	G34174	130	132	0.55	0.18	9	0.01	10	42	0.1	164	AS7-5442a
M-07-26	G34175	132	134	0.61	0.20	8	0.8	15	26	0.1	175	AS7-5442a
M-07-26	G34176	134	136	0.50	0.14	11	0.3	15	30	0.1	167	AS7-5442a
M-07-26	G34177	136	138	0.74	0.16	12	0.01	10	28	0.1	131	AS7-5442a
M-07-26	G34178	138	140	0.60	0.14	11	0.6	10	28	0.1	137	AS7-5442a
M-07-26	G34179	140	142	0.37	0.14	14	0.01	15	22	0.1	205	AS7-5442a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-26	G34180	142	143	0.71	0.26	16	0.2	10	18	0.1	182	AS7-5442a
M-07-26	G34181	143	145	0.62	0.24	21	1.1	10	36	5	108	AS7-5442a
M-07-26	G34182	145	147	0.43	0.14	15	0.4	10	26	0.1	94	AS7-5442a
M-07-26	G34183	147	149	0.66	0.26	13	2.7	15	34	5	72	AS7-5442a
M-07-26	G34184	149	151	0.52	0.38	8	2.3	140	56	100	180	AS7-5442a
M-07-26	G34185	151	153	0.74	0.24	49	0.01	15	104	5	288	AS7-5442a
M-07-26	G34186	153	155	0.52	0.24	11	0.01	10	54	0.1	70	AS7-5442a
M-07-26	G34187	155	157	0.55	0.25	13	0.9	10	32	0.1	40	AS7-5442a
M-07-26	G34188	157	159	0.87	0.27	16	0.01	10	32	0.1	93	AS7-5442a
M-07-26	G34189	159	161	0.64	0.16	14	0.2	10	22	0.1	63	AS7-5442a
M-07-26	G34190	161	163	0.92	0.31	14	0.4	10	42	0.1	95	AS7-5442a
M-07-26	G34191	163	165	0.47	0.24	22	0.01	10	34	0.1	84	AS7-5442a
M-07-26	G34193	165	167	0.54	0.29	20	0.4	15	50	5	79	AS7-5442a
M-07-26	G34194	167	169	0.44	0.19	26	2.1	10	26	0.1	58	AS7-5442a
M-07-26	G34195	169	171	0.56	0.15	17	0.01	10	14	0.1	74	AS7-5442a
M-07-26	G34196	171	173	0.49	0.13	22	10.8	10	24	0.1	124	AS7-5442a
M-07-26	G34197	173	175	0.46	0.15	26	1.5	10	30	0.1	123	AS7-5442a
M-07-26	G34198	175	177	0.73	0.22	18	2.3	10	26	0.1	85	AS7-5442a
M-07-26	G34199	177	179	0.56	0.19	22	2.7	30	24	10	123	AS7-5442a
M-07-26	G34200	179	181	0.55	0.20	13	1.4	35	32	15	118	AS7-5442a
M-07-26	G34201	181	183	0.54	0.14	15	1.4	25	36	0.1	154	AS7-5451a
M-07-26	G34202	183	185	0.73	0.20	19	2.1	25	52	0.1	123	AS7-5451a
M-07-26	G34203	185	187	1.34	0.22	15	2.4	55	38	0.1	191	AS7-5451a
M-07-26	G34204	187	189	0.98	0.25	11	4.5	75	60	0.1	434	AS7-5451a
M-07-26	G34205	189	191	2.50	0.35	12	10.3	30	166	0.1	368	AS7-5451a
M-07-26	G34206	191	193	0.69	0.24	16	2.1	35	32	0.1	136	AS7-5451a
M-07-26	G34207	193	195	2.06	0.20	14	6.1	80	200	0.1	92	AS7-5451a
M-07-26	G34208	195	197	0.76	0.16	18	2	35	52	0.1	83	AS7-5451a
M-07-26	G34209	197	198.5	0.67	0.14	19	1.1	30	42	0.1	151	AS7-5451a
M-07-26	G34210	198.5	199.65	1.44	0.20	13	1.9	50	60	0.1	187	AS7-5451a
M-07-26	G34211	199.65	201	1.07	0.19	11	5	95	90	0.1	164	AS7-5451a
M-07-26	G34213	201	203	1.32	0.11	14	13.7	280	54	40	132	AS7-5451a
M-07-26	G34214	203	205	0.85	0.13	21	8.8	170	42	10	158	AS7-5451a
M-07-26	G34215	205	207	0.59	0.15	12	6.7	155	48	0.1	156	AS7-5451a
M-07-26	G34216	207	209	1.42	0.18	15	7	105	44	0.1	183	AS7-5451a
M-07-26	G34217	209	211	0.94	0.28	8	9	70	84	0.1	168	AS7-5451a
M-07-26	G34219	211	213	8.40	0.15	18	28.6	475	576	100	1805	AS7-5451a
M-07-26	G34220	213	215	3.90	0.19	14	27.3	400	154	100	700	AS7-5451a
M-07-26	G34221	215	216.25	0.89	0.21	8	7.1	60	74	0.1	304	AS7-5451a
M-07-26	G34222	216.25	218	0.70	0.17	13	4.1	50	78	0.1	281	AS7-5451a
M-07-26	G34223	218	220	0.44	0.11	15	3	40	128	0.1	560	AS7-5451a
M-07-26	G34224	220	222	0.87	0.20	13	9	45	164	0.1	524	AS7-5451a
M-07-26	G34226	222	224.1	1.85	0.42	24	9.8	30	128	0.1	551	AS7-5451a
M-07-26	G34227	224.1	226	0.61	0.18	24	17	90	114	20	295	AS7-5451a
M-07-26	G34228	226	228	0.62	0.16	16	8	85	112	5	300	AS7-5451a
M-07-26	G34229	228	229.25	0.57	0.23	131	7.2	45	100	0.1	210	AS7-5451a
M-07-26	G34230	229.25	231	0.71	0.17	31	4.6	30	156	0.1	602	AS7-5451a
M-07-26	G34231	231	233	0.52	0.14	23	3.7	60	120	0.1	526	AS7-5451a
M-07-26	G34232	233	235	1.29	0.21	22	0.8	80	70	0.1	145	AS7-5451a
M-07-26	G34233	235	237	0.70	0.15	21	0.8	70	82	0.1	172	AS7-5451a
M-07-26	G34234	237	239	0.81	0.30	16	1.1	90	234	15	194	AS7-5451a
M-07-26	G34235	239	241	0.53	0.20	21	4.8	45	80	0.1	157	AS7-5451a
M-07-26	G34236	241	243	0.60	0.22	21	11.7	70	174	25	184	AS7-5454a
M-07-26	G34237	243	245	0.52	0.16	24	2.9	25	44	0.1	98	AS7-5454a
M-07-26	G34238	245	246.5	0.94	0.16	50	2.5	140	36	0.1	136	AS7-5454a
M-07-26	G34239	246.5	247.75	0.60	0.20	30	3	40	76	0.1	148	AS7-5454a
M-07-26	G34240	247.75	249.5	0.58	0.21	52	2.8	5	40	0.1	75	AS7-5454a
M-07-26	G34241	249.5	251.3	0.90	0.20	22	2	55	34	0.1	37	AS7-5454a
M-07-26	G34242	251.3	253	0.60	0.12	65	0.8	0.1	36	0.1	81	AS7-5454a
M-07-26	G34243	253	254.5	0.60	0.15	39	0.8	0.1	32	0.1	56	AS7-5454a
M-07-26	G34244	254.5	256.15	1.02	0.23	43	1.3	0.1	60	0.1	84	AS7-5454a
M-07-26	G34245	256.15	258	0.69	0.19	52	1.3	5	46	0.1	123	AS7-5454a
M-07-26	G34247	258	260	0.68	0.17	54	1.2	10	76	0.1	186	AS7-5454a
M-07-26	G34248	260	262	0.90	0.22	42	1.3	0.1	72	0.1	127	AS7-5454a
M-07-26	G34249	262	264	0.57	0.15	58	0.8	0.1	48	0.1	136	AS7-5454a
M-07-26	G34250	264	266	0.77	0.25	83	1.6	0.1	44	0.1	71	AS7-5454a
M-07-26	G34251	266	268	1.06	0.27	95	3.4	0.1	48	0.1	132	AS7-5454a
M-07-26	G34252	268	269.6	0.67	0.24	55	2.6	5	30	0.1	134	AS7-5454a
M-07-26	G34253	269.6	271	0.52	0.25	23	2.3	0.1	48	0.1	40	AS7-5454a
M-07-26	G34254	271	273	0.71	0.27	46	4	80	28	10	41	AS7-5454a
M-07-26	G34256	273	275	0.70	0.20	37	2	20	36	0.1	78	AS7-5454a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-26	G34257	275	277	0.58	0.22	40	1.9	10	24	0.1	67	AS7-5454a
M-07-26	G34258	277	279	0.86	0.22	42	1.8	0.1	30	0.1	77	AS7-5454a
M-07-26	G34259	279	281	0.53	0.15	78	1.5	20	42	0.1	73	AS7-5454a
M-07-26	G34260	281	283	0.53	0.25	41	2.1	0.1	36	0.1	45	AS7-5454a
M-07-26	G34261	283	285	0.79	0.24	42	3	80	32	0.1	40	AS7-5454a
M-07-26	G34262	285	287	3.20	0.20	19	5.8	235	34	0.1	137	AS7-5454a
M-07-26	G34263	287	289	1.34	0.23	24	2.5	115	24	0.1	16	AS7-5454a
M-07-26	G34264	289	291	0.91	0.27	13	3.5	115	32	0.1	25	AS7-5454a
M-07-26	G34265	291	293	0.91	0.26	11	9.5	305	34	40	89	AS7-5454a
M-07-26	G34266	293	295	0.61	0.28	15	3.5	15	24	0.1	39	AS7-5454a
M-07-26	G34267	295	297	0.44	0.21	29	2.9	85	38	0.1	83	AS7-5454a
M-07-26	G34268	297	299	0.82	0.21	48	3.7	65	16	0.1	45	AS7-5454a
M-07-26	G34269	299	301	0.69	0.19	37	10.3	110	42	0.1	71	AS7-5454a
M-07-26	G34270	301	303	0.95	0.26	34	7.4	60	30	0.1	61	AS7-5454a
M-07-26	G34271	303	305	1.36	0.27	31	2.8	0.1	20	0.1	53	AS7-5455a
M-07-26	G34272	305	307	0.90	0.23	27	3.7	20	24	0.1	36	AS7-5455a
M-07-26	G34274	307	309	0.72	0.17	32	1.8	0.1	20	0.1	28	AS7-5455a
M-07-26	G34275	309	311	1.23	0.28	19	1.7	0.1	20	0.1	32	AS7-5455a
M-07-26	G34276	311	313	0.84	0.15	27	1.5	0.1	22	0.1	33	AS7-5455a
M-07-26	G34277	313	315	0.92	0.14	27	1.2	0.1	22	0.1	32	AS7-5455a
M-07-26	G34278	315	317	0.71	0.15	25	1.5	0.1	20	0.1	47	AS7-5455a
M-07-26	G34279	317	319	0.67	0.21	17	4	0.1	18	0.1	23	AS7-5455a
M-07-26	G34280	319	321	0.63	0.15	29	3.2	35	60	0.1	123	AS7-5455a
M-07-26	G34281	321	323	0.49	0.18	30	2.2	20	54	0.1	71	AS7-5455a
M-07-26	G34282	323	325	0.46	0.18	14	1.5	0.1	30	0.1	42	AS7-5455a
M-07-26	G34283	325	327	0.45	0.20	17	1.4	0.1	26	0.1	56	AS7-5455a
M-07-26	G34284	327	329	0.58	0.19	13	2.3	0.1	50	0.1	116	AS7-5455a
M-07-26	G34286	329	331	0.86	0.16	29	3.4	30	52	0.1	83	AS7-5455a
M-07-26	G34287	331	332.2	0.65	0.18	39	2.2	0.1	26	0.1	57	AS7-5455a
M-07-26	G34288	332.2	333.5	0.57	0.14	32	2.6	25	36	5	115	AS7-5455a
M-07-26	G34289	333.5	337	0.58	0.28	35	2.1	10	78	0.1	79	AS7-5455a
M-07-26	G34290	337	339	0.55	0.23	29	1.8	10	50	0.1	49	AS7-5455a
M-07-26	G34291	339	341	0.60	0.19	37	3.2	0.1	70	0.1	314	AS7-5455a
M-07-26	G34292	341	343	0.68	0.20	43	2.9	0.1	84	0.1	253	AS7-5455a
M-07-26	G34293	343	345	0.55	0.17	32	1.5	0.1	46	0.1	54	AS7-5455a
M-07-26	G34294	345	347	0.56	0.15	21	1.7	15	30	0.1	117	AS7-5455a
M-07-26	G34295	347	349	0.38	0.23	34	1.6	0.1	42	0.1	79	AS7-5455a
M-07-26	G34296	349	351	0.48	0.21	25	1.4	0.1	24	0.1	57	AS7-5455a
M-07-26	G34298	351	353	0.65	0.26	46	1.8	0.1	28	0.1	55	AS7-5455a
M-07-26	G34299	353	355	0.40	0.21	35	1.9	0.1	24	0.1	67	AS7-5455a
M-07-26	G34300	355	357	0.59	0.20	29	2	0.1	34	0.1	86	AS7-5455a
M-07-26	G34301	357	359	0.58	0.22	106	1.8	0.1	18	0.1	139	AS7-5455a
M-07-26	G34302	359	361	0.61	0.18	68	1.9	0.1	32	0.1	294	AS7-5455a
M-07-26	G34303	361	363	0.86	0.21	41	3.2	0.1	38	0.1	38	AS7-5455a
M-07-26	G34304	363	365	0.96	0.18	46	4.3	0.1	26	0.1	39	AS7-5455a
M-07-26	G34305	365	367	0.90	0.22	117	3.8	15	26	0.1	42	AS7-5455a
M-07-26	G34306	367	369	1.02	0.27	48	2.9	15	30	0.1	65	AS7-5456a
M-07-26	G34307	369	371	0.66	0.22	86	2.4	50	26	10	47	AS7-5456a
M-07-26	G34308	371	373	0.91	0.23	84	2.2	15	20	0.1	40	AS7-5456a
M-07-26	G34309	373	375	0.91	0.21	52	2	25	22	0.1	36	AS7-5456a
M-07-26	G34310	375	376.2	0.83	0.22	49	3.2	35	158	10	1417	AS7-5456a
M-07-26	G34311	376.2	377.9	0.00	0.00	0.1	0.01	60	24	0.1	140	AS7-5456a
M-07-26	G34312	377.9	379	1.11	0.37	155	2.3	70	20	0.1	38	AS7-5456a
M-07-26	G34313	379	381	0.82	0.22	95	1.5	15	20	0.1	26	AS7-5456a
M-07-26	G34315	381	383	0.99	0.22	75	1.5	20	18	0.1	41	AS7-5456a
M-07-26	G34316	383	385	0.97	0.27	120	1.9	45	20	0.1	29	AS7-5456a
M-07-26	G34317	385	387	1.10	0.25	76	2.3	85	22	10	22	AS7-5456a
M-07-26	G34318	387	388.15	1.02	0.24	62	1.9	20	20	0.1	37	AS7-5456a
M-07-26	G34319	388.15	390	1.53	0.31	65	1.9	25	20	0.1	59	AS7-5456a
M-07-26	G34320	390	392	0.90	0.25	119	1.7	20	26	0.1	40	AS7-5456a
M-07-26	G34321	392	394	0.74	0.21	55	1.3	20	20	0.1	43	AS7-5456a
M-07-26	G34322	394	396	0.81	0.21	35	1.4	15	28	0.1	33	AS7-5456a
M-07-26	G34323	396	398	0.95	0.27	54	1.4	15	24	0.1	57	AS7-5456a
M-07-26	G34324	398	399.55	1.05	0.18	97	1.1	15	16	0.1	58	AS7-5456a
M-07-26	G34325	399.55	401	1.08	0.24	97	1.8	20	20	0.1	42	AS7-5456a
M-07-26	G34326	401	403	0.85	0.26	43	3	20	32	0.1	47	AS7-5456a
M-07-26	G34328	403	405	1.03	0.19	61	1.7	15	42	0.1	62	AS7-5456a
M-07-26	G34329	405	407	0.52	0.15	78	1.2	15	20	0.1	53	AS7-5456a
M-07-26	G34330	407	409	1.00	0.26	120	2.4	10	24	0.1	35	AS7-5456a
M-07-26	G34331	409	411	0.90	0.20	53	3.1	15	30	0.1	31	AS7-5456a
M-07-26	G34332	411	413	1.22	0.19	87	1.4	15	28	0.1	38	AS7-5456a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-26	G34333	413	415	0.50	0.16	66	1.4	15	24	0.1	43	AS7-5456a
M-07-26	G34334	415	416.3	0.78	0.20	59	2.3	15	22	0.1	49	AS7-5456a
M-07-26	G34335	416.3	417.6	1.12	0.26	63	4.7	20	20	0.1	53	AS7-5456a
M-07-26	G34336	417.6	419	0.45	0.13	57	17	20	92	0.1	141	AS7-5456a
M-07-26	G34338	419	421	0.44	0.15	49	5.7	20	26	0.1	52	AS7-5456a
M-07-26	G34339	421	423	0.53	0.18	82	8.7	25	122	5	22	AS7-5456a
M-07-26	G34340	423	424.2	0.32	0.15	42	4.4	20	50	0.1	21	AS7-5456a
M-07-26	G34341	424.2	426	0.67	0.18	58	2.4	5	30	0.1	42	AS7-5459a
M-07-26	G34342	426	428	0.42	0.15	26	2.9	10	32	0.1	59	AS7-5459a
M-07-26	G34343	428	430	0.78	0.09	100	1	20	38	5	48	AS7-5459a
M-07-26	G34344	430	432	0.38	0.15	34	1.3	10	26	0.1	43	AS7-5459a
M-07-26	G34345	432	434	0.40	0.12	37	1.8	40	40	0.1	51	AS7-5459a
M-07-26	G34346	434	436	0.58	0.11	61	1.6	35	36	0.1	68	AS7-5459a
M-07-26	G34347	436	438	0.78	0.10	45	1.9	10	20	0.1	46	AS7-5459a
M-07-26	G34348	438	440	0.46	0.23	35	2.6	20	34	0.1	56	AS7-5459a
M-07-26	G34349	440	442	0.62	0.12	135	1.7	20	32	0.1	60	AS7-5459a
M-07-26	G34350	442	444	0.95	0.15	116	2.1	20	34	5	57	AS7-5459a
M-07-26	G34351	444	446	0.65	0.17	69	2.6	25	58	0.1	48	AS7-5459a
M-07-26	G34352	446	448	0.47	0.12	94	1	15	38	0.1	59	AS7-5459a
M-07-26	G34353	448	450	0.48	0.14	79	1.1	25	44	0.1	78	AS7-5459a
M-07-26	G34355	450	452	0.50	0.12	52	1	35	36	0.1	78	AS7-5459a
M-07-26	G34356	452	454	0.45	0.12	68	1.4	30	42	0.1	82	AS7-5459a
M-07-26	G34357	454	456	0.55	0.14	63	1.6	45	42	0.1	68	AS7-5459a
M-07-26	G34358	456	458	0.46	0.09	58	1.4	35	38	0.1	66	AS7-5459a
M-07-26	G34359	458	460	0.60	0.18	100	2.5	40	48	0.1	65	AS7-5459a
M-07-26	G34361	460	462	0.56	0.16	64	1.8	20	46	0.1	51	AS7-5459a
M-07-26	G34362	462	464	0.63	0.14	41	1.9	25	38	0.1	95	AS7-5459a
M-07-26	G34363	464	466	0.41	0.11	207	1.3	40	56	0.1	314	AS7-5459a
M-07-26	G34364	466	468	0.55	0.14	90	1.3	30	38	0.1	68	AS7-5459a
M-07-26	G34365	468	470	0.40	0.11	84	1.1	30	36	0.1	87	AS7-5459a
M-07-26	G34366	470	471.4	0.55	0.13	53	1.2	40	40	0.1	74	AS7-5459a
M-07-26	G34367	471.4	472.72	0.55	0.13	115	1.2	20	42	0.1	81	AS7-5459a
M-07-27	G36126	5.8	7.8	0.00	0.03	4	0.5	10	6	0.1	38	AS7-5437a
M-07-27	G36127	7.8	10	0.03	0.04	2	0.4	20	8	0.1	27	AS7-5437a
M-07-27	G36128	10	12	0.09	0.11	3	1.1	25	22	0.1	34	AS7-5437a
M-07-27	G36129	12	14	0.00	0.02	2	0.01	25	12	0.1	96	AS7-5437a
M-07-27	G36130	14	16	0.00	0.00	0.1	0.01	20	10	0.1	81	AS7-5437a
M-07-27	G36131	16	18	0.00	0.00	0.1	0.01	20	10	0.1	78	AS7-5437a
M-07-27	G36132	18	20	0.24	0.07	2	0.9	40	28	0.1	46	AS7-5437a
M-07-27	G36133	20	21.3	0.21	0.04	2	0.7	20	14	0.1	41	AS7-5437a
M-07-27	G36134	21.3	22.6	0.28	0.08	2	1.3	60	26	0.1	51	AS7-5437a
M-07-27	G36135	22.6	24.6	0.07	0.06	6	0.8	10	14	0.1	27	AS7-5437a
M-07-27	G36136	24.6	26.6	0.04	0.06	6	0.6	5	12	0.1	20	AS7-5437a
M-07-27	G36137	26.6	28.6	0.05	0.08	4	0.6	5	8	0.1	19	AS7-5437a
M-07-27	G36138	28.6	30.6	0.05	0.07	5	0.7	5	10	0.1	27	AS7-5437a
M-07-27	G36139	30.6	32.6	0.06	0.07	6	0.8	5	14	0.1	24	AS7-5437a
M-07-27	G36141	32.6	34.6	0.03	0.07	3	0.4	10	8	0.1	37	AS7-5437a
M-07-27	G36142	34.6	36.6	0.05	0.08	5	0.4	5	8	0.1	24	AS7-5437a
M-07-27	G36143	36.6	38.6	0.13	0.12	14	1.3	20	20	0.1	32	AS7-5437a
M-07-27	G36145	38.6	40.6	0.10	0.14	6	1.2	10	12	0.1	42	AS7-5437a
M-07-27	G36146	40.6	42.6	1.80	0.85	598	3.8	35	58	20	84	AS7-5437a
M-07-27	G36147	42.6	44	0.16	0.17	18	1.4	10	12	0.1	33	AS7-5437a
M-07-27	G36148	44	45.2	0.05	0.09	1	0.5	10	14	0.1	55	AS7-5437a
M-07-27	G36149	45.2	47	0.08	0.10	0.1	0.4	10	24	0.1	66	AS7-5437a
M-07-27	G36150	47	49	0.07	0.13	0.1	0.5	10	20	0.1	52	AS7-5437a
M-07-27	G36151	49	51	0.05	0.07	0.1	0.6	15	32	0.1	84	AS7-5438a
M-07-27	G36152	51	52.6	0.12	0.03	0.1	0.5	25	14	0.1	49	AS7-5438a
M-07-27	G36153	52.6	54	0.05	0.06	7	0.4	10	10	0.1	32	AS7-5438a
M-07-27	G36154	54	56	0.00	0.04	1	0.2	5	6	0.1	33	AS7-5438a
M-07-27	G36155	56	58	0.00	0.06	7	0.2	10	10	0.1	26	AS7-5438a
M-07-27	G36156	58	60	0.06	0.09	1	0.4	10	16	0.1	54	AS7-5438a
M-07-27	G36157	60	62	0.04	0.09	2	0.4	15	20	0.1	82	AS7-5438a
M-07-27	G36158	62	64	0.00	0.09	4	0.3	10	14	0.1	60	AS7-5438a
M-07-27	G36159	64	66	0.07	0.10	3	0.5	10	18	0.1	38	AS7-5438a
M-07-27	G36160	66	68	0.09	0.10	2	0.6	10	12	0.1	47	AS7-5438a
M-07-27	G36161	68	68.93	0.15	0.20	10	1	25	26	0.1	63	AS7-5438a
M-07-27	G36162	68.93	70	0.04	0.04	2	0.01	5	10	0.1	37	AS7-5438a
M-07-27	G36163	70	72	0.10	0.11	2	0.5	10	24	0.1	60	AS7-5438a
M-07-27	G36164	72	74	0.15	0.14	3	0.7	5	30	0.1	38	AS7-5438a
M-07-27	G36165	74	76	0.10	0.14	0.1	0.8	15	24	0.1	72	AS7-5438a
M-07-27	G36166	76	78	0.00	0.03	1	0.2	20	12	0.1	54	AS7-5438a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-27	G36167	78	80	0.00	0.00	2	0.01	15	8	0.1	62	AS7-5438a
M-07-27	G36168	80	81	0.00	0.00	0.1	0.01	15	10	0.1	63	AS7-5438a
M-07-27	G36169	81	82.5	0.00	0.00	1	0.01	20	10	0.1	61	AS7-5438a
M-07-27	G36170	82.5	84.4	0.00	0.00	0.1	0.01	15	12	0.1	51	AS7-5438a
M-07-27	G36171	84.4	86.25	0.00	0.00	2	0.01	20	12	0.1	50	AS7-5438a
M-07-27	G36172	86.25	88	0.06	0.08	29	0.9	75	34	0.1	41	AS7-5438a
M-07-27	G36173	88	89.1	0.23	0.15	31	2.3	50	40	5	49	AS7-5438a
M-07-27	G36174	89.1	91.5	0.05	0.10	12	2.1	15	270	0.1	90	AS7-5438a
M-07-27	G36175	91.5	93.87	0.08	0.13	10	2.2	15	116	0.1	83	AS7-5438a
M-07-27	G36176	93.87	95	0.19	0.20	6	2.7	15	206	0.1	163	AS7-5438a
M-07-27	G36178	95	97	0.10	0.14	25	2.7	15	296	0.1	139	AS7-5438a
M-07-27	G36179	97	99	0.07	0.13	23	4	15	300	0.1	171	AS7-5438a
M-07-27	G36180	99	101	0.04	0.12	11	2.2	10	232	0.1	184	AS7-5438a
M-07-27	G36181	101	103	0.05	0.10	34	1.9	15	332	0.1	195	AS7-5438a
M-07-27	G36182	103	105	0.08	0.11	12	2	15	352	0.1	279	AS7-5438a
M-07-27	G36184	105	107	0.04	0.11	5	2.4	10	518	0.1	176	AS7-5438a
M-07-27	G36185	107	109	0.07	0.09	9	2.1	10	300	0.1	122	AS7-5438a
M-07-27	G36186	109	111	0.47	0.14	37	4.2	20	480	0.1	194	AS7-5439a
M-07-27	G36187	111	113	0.20	0.14	17	2.8	15	116	0.1	147	AS7-5439a
M-07-27	G36188	113	115	0.08	0.19	23	2.6	10	108	0.1	105	AS7-5439a
M-07-27	G36189	115	117	0.14	0.10	4	9	10	686	0.1	162	AS7-5439a
M-07-27	G36190	117	119	0.20	0.15	7	5.8	20	134	0.1	98	AS7-5439a
M-07-27	G36191	119	121	0.14	0.18	18	2.2	20	50	0.1	86	AS7-5439a
M-07-27	G36192	121	123	0.12	0.13	19	4.6	30	122	0.1	113	AS7-5439a
M-07-27	G36193	123	125	0.12	0.10	25	2.8	30	68	0.1	140	AS7-5439a
M-07-27	G36194	125	127	0.36	0.32	14	4	15	44	0.1	101	AS7-5439a
M-07-27	G36195	127	129	0.25	0.18	36	2.6	25	206	0.1	124	AS7-5439a
M-07-27	G36196	129	131	0.11	0.13	17	5.6	20	250	0.1	184	AS7-5439a
M-07-27	G36198	131	133	0.07	0.12	29	9.8	20	416	0.1	350	AS7-5439a
M-07-27	G36199	133	135	0.10	0.07	33	4	15	266	0.1	67	AS7-5439a
M-07-27	G36200	135	137	0.18	0.08	10	2.8	25	100	0.1	86	AS7-5439a
M-07-27	G36201	137	139	0.14	0.13	18	3	15	108	0.1	119	AS7-5439a
M-07-27	G36202	139	141	0.31	0.09	37	3.4	15	130	0.1	115	AS7-5439a
M-07-27	G36203	141	143	0.11	0.07	72	2.8	30	96	0.1	126	AS7-5439a
M-07-27	G36205	143	145	0.11	0.07	58	5.4	15	164	0.1	148	AS7-5439a
M-07-27	G36206	145	147	0.06	0.03	37	1.2	10	80	0.1	99	AS7-5439a
M-07-27	G36207	147	149	0.86	0.29	12	7.8	20	294	0.1	337	AS7-5439a
M-07-27	G36208	149	151	0.21	0.11	22	2.2	15	62	0.1	127	AS7-5439a
M-07-27	G36209	151	153	0.21	0.10	56	2.4	15	82	0.1	104	AS7-5439a
M-07-27	G36210	153	155	0.51	0.16	42	2.8	25	90	0.1	170	AS7-5439a
M-07-27	G36211	155	157	0.17	0.13	20	3	30	144	0.1	109	AS7-5439a
M-07-27	G36212	157	159	0.15	0.08	23	1.8	30	52	0.1	74	AS7-5439a
M-07-27	G36213	159	161	0.16	0.13	45	2.4	30	116	0.1	71	AS7-5439a
M-07-27	G36214	161	163	0.34	0.06	15	3.8	40	244	0.1	122	AS7-5439a
M-07-27	G36215	163	165	0.21	0.03	28	3.2	45	294	0.1	161	AS7-5439a
M-07-27	G36217	165	167	0.40	0.07	5	6.4	50	194	0.1	282	AS7-5439a
M-07-27	G36218	167	169	0.34	0.22	2	7.2	50	38	0.1	135	AS7-5439a
M-07-27	G36219	169	170.5	0.28	0.09	2	5	35	30	0.1	100	AS7-5439a
M-07-27	G36220	170.5	171.92	0.11	0.07	3	2.4	30	16	0.1	102	AS7-5439a
M-07-27	G36221	171.92	173.92	0.12	0.02	3	1.4	15	18	0.1	3	AS7-5449a
M-07-27	G36222	173.92	175.92	0.18	0.04	7	2.3	10	24	0.1	11	AS7-5449a
M-07-27	G36223	175.92	177.92	0.14	0.07	11	2.7	15	26	10	44	AS7-5449a
M-07-27	G36224	177.92	179.85	0.10	0.12	7	2.7	10	42	0.1	27	AS7-5449a
M-07-27	G36225	179.85	180.44	0.25	0.16	34	4.8	10	176	10	23	AS7-5449a
M-07-27	G36226	180.44	182	0.71	0.20	39	2.3	5	18	0.1	27	AS7-5449a
M-07-27	G36227	182	184	0.66	0.27	84	2.7	0.1	32	0.1	56	AS7-5449a
M-07-27	G36228	184	186	0.95	0.17	76	1.8	5	24	0.1	42	AS7-5449a
M-07-27	G36229	186	188	0.60	0.22	45	2.6	10	38	5	76	AS7-5449a
M-07-27	G36230	188	190	0.95	0.21	35	2.5	10	34	0.1	71	AS7-5449a
M-07-27	G36231	190	192	0.62	0.22	52	2.2	10	26	10	53	AS7-5449a
M-07-27	G36232	192	194	1.82	0.20	35	2.2	0.1	40	0.1	100	AS7-5449a
M-07-27	G36233	194	196	0.86	0.21	35	1.9	0.1	38	0.1	108	AS7-5449a
M-07-27	G36234	196	198	0.89	0.23	50	2.1	0.1	26	5	65	AS7-5449a
M-07-27	G36235	198	200	0.54	0.15	52	3.3	15	42	0.1	122	AS7-5449a
M-07-27	G36237	200	202	0.65	0.23	50	6.5	30	40	5	1436	AS7-5449a
M-07-27	G36238	202	204	0.34	0.12	116	4.2	20	22	0.1	79	AS7-5449a
M-07-27	G36239	204	205.13	0.66	0.17	68	3.5	30	18	0.1	40	AS7-5449a
M-07-27	G36240	205.13	207	0.58	0.14	111	3.5	20	70	5	161	AS7-5449a
M-07-27	G36242	207	209	0.41	0.16	138	2.1	10	28	15	40	AS7-5449a
M-07-27	G36243	209	211	0.47	0.17	57	2.5	15	32	0.1	46	AS7-5449a
M-07-27	G36244	211	213	0.47	0.13	39	3.1	20	30	5	124	AS7-5449a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-27	G36245	213	215	1.01	0.09	59	8.7	265	54	15	331	AS7-5449a
M-07-27	G36246	215	217	0.45	0.14	26	6.1	30	42	5	132	AS7-5449a
M-07-27	G36247	217	219	1.30	0.18	49	4.8	165	46	10	176	AS7-5449a
M-07-27	G36248	219	221	0.58	0.15	115	1.4	30	44	10	68	AS7-5449a
M-07-27	G36249	221	223	0.55	0.17	85	1.3	5	36	0.1	51	AS7-5449a
M-07-27	G36250	223	225	0.29	0.15	221	2.1	15	68	0.1	81	AS7-5449a
M-07-27	G36251	225	227	0.20	0.13	12	1.4	15	34	0.1	44	AS7-5449a
M-07-27	G36252	227	229	0.44	0.14	44	1.7	20	74	5	285	AS7-5449a
M-07-27	G36253	229	231	0.41	0.24	50	1.9	25	42	15	85	AS7-5449a
M-07-27	G36254	231	233	0.21	0.09	78	1.4	20	30	10	82	AS7-5449a
M-07-27	G36255	233	234.55	0.27	0.10	53	1.7	15	56	10	91	AS7-5449a
M-07-27	G36256	234.55	236	0.55	0.13	78	1.9	5	34	0.1	57	AS7-5450a
M-07-27	G36257	236	238	0.58	0.11	160	1.5	15	90	0.1	93	AS7-5450a
M-07-27	G36258	238	240	0.23	0.09	26	1.1	10	72	0.1	132	AS7-5450a
M-07-27	G36259	240	242	0.46	0.13	44	1.7	0.1	42	0.1	55	AS7-5450a
M-07-27	G36260	242	244	0.33	0.11	39	1.1	15	82	0.1	70	AS7-5450a
M-07-27	G36261	244	246	0.33	0.13	42	1	5	30	0.1	47	AS7-5450a
M-07-27	G36262	246	248	0.27	0.09	66	0.8	10	32	0.1	61	AS7-5450a
M-07-27	G36263	248	250	0.12	0.08	18	0.6	0.1	32	0.1	73	AS7-5450a
M-07-27	G36265	250	252	0.23	0.10	44	0.7	0.1	28	0.1	56	AS7-5450a
M-07-27	G36267	252	254	0.08	0.07	38	0.6	10	24	0.1	65	AS7-5450a
M-07-27	G36268	254	255	0.08	0.06	24	0.6	5	22	0.1	56	AS7-5450a
M-07-27	G36269	255	256.25	0.24	0.12	16	1.7	25	34	0.1	81	AS7-5450a
M-07-27	G36270	256.25	258	0.26	0.13	29	1	0.1	34	0.1	44	AS7-5450a
M-07-27	G36271	258	260	0.21	0.10	27	0.7	5	28	0.1	58	AS7-5450a
M-07-27	G36272	260	262	0.15	0.11	23	0.6	0.1	32	0.1	52	AS7-5450a
M-07-27	G36273	262	264	0.17	0.13	54	1	25	62	0.1	94	AS7-5450a
M-07-27	G36274	264	266	0.33	0.12	72	1.1	30	28	0.1	322	AS7-5450a
M-07-27	G36275	266	267.61	0.42	0.15	51	1.1	0.1	30	0.1	34	AS7-5450a
M-07-27	G36276	267.61	269	0.36	0.14	13	0.9	0.1	28	0.1	30	AS7-5450a
M-07-27	G36277	269	271	0.12	0.09	11	0.5	10	34	0.1	84	AS7-5450a
M-07-27	G36278	271	273	0.24	0.10	17	0.9	10	30	0.1	78	AS7-5450a
M-07-27	G36279	273	275	0.27	0.11	61	1.3	0.1	40	0.1	74	AS7-5450a
M-07-27	G36281	275	277	0.23	0.11	43	1	10	30	0.1	34	AS7-5450a
M-07-27	G36282	277	279	0.21	0.10	69	1.3	0.1	96	0.1	119	AS7-5450a
M-07-27	G36283	279	281	0.13	0.08	92	0.7	10	28	0.1	56	AS7-5450a
M-07-27	G36284	281	283	0.17	0.10	36	1.1	15	34	0.1	52	AS7-5450a
M-07-27	G36285	283	284.52	0.15	0.12	35	1.7	5	72	0.1	44	AS7-5450a
M-07-27	G36286	284.52	286	0.26	0.12	63	1.2	10	26	0.1	44	AS7-5450a
M-07-27	G36287	286	288	0.16	0.09	56	0.8	5	22	0.1	35	AS7-5450a
M-07-27	G36288	288	290	0.15	0.10	19	0.9	5	22	0.1	45	AS7-5450a
M-07-27	G36289	290	292	0.13	0.08	67	0.6	5	22	0.1	48	AS7-5450a
M-07-27	G36290	292	294	0.08	0.07	68	0.6	5	24	0.1	47	AS7-5450a
M-07-27	G36291	294	296	0.14	0.08	46	0.01	0.1	24	0.1	45	AS7-5455a
M-07-27	G36292	296	298	0.13	0.07	19	0.5	0.1	18	5	47	AS7-5457a
M-07-27	G36293	298	300	0.12	0.09	13	0.5	5	26	0.1	69	AS7-5457a
M-07-27	G36294	300	302	0.15	0.08	96	0.6	15	26	0.1	57	AS7-5457a
M-07-27	G36295	302	304	0.17	0.07	48	0.8	0.1	20	0.1	49	AS7-5457a
M-07-27	G36296	304	306	0.13	0.06	20	0.7	15	22	5	57	AS7-5457a
M-07-27	G36297	306	308	0.19	0.06	28	0.7	10	26	5	60	AS7-5457a
M-07-27	G36298	308	310	0.35	0.13	33	1.3	50	24	0.1	55	AS7-5457a
M-07-27	G36299	310	312	0.36	0.14	205	1.6	5	28	0.1	32	AS7-5457a
M-07-27	G36300	312	314	0.27	0.09	91	0.7	0.1	22	0.1	33	AS7-5457a
M-07-27	G36302	314	316	0.19	0.10	68	0.7	0.1	26	0.1	37	AS7-5457a
M-07-27	G36303	316	318	0.23	0.09	25	0.7	0.1	28	0.1	44	AS7-5457a
M-07-27	G36304	318	320	0.17	0.09	17	0.9	10	26	0.1	55	AS7-5457a
M-07-27	G36305	320	322	0.25	0.12	27	0.8	0.1	34	0.1	38	AS7-5457a
M-07-27	G36306	322	324	0.12	0.07	34	0.5	10	28	0.1	47	AS7-5457a
M-07-27	G36307	324	326	0.29	0.10	26	0.8	10	34	0.1	60	AS7-5457a
M-07-27	G36308	326	328	0.26	0.11	21	1.1	0.1	28	0.1	67	AS7-5457a
M-07-27	G36309	328	330	0.21	0.09	32	0.9	0.1	24	0.1	62	AS7-5457a
M-07-27	G36310	330	332	0.30	0.10	306	1	5	24	0.1	62	AS7-5457a
M-07-27	G36311	332	334	0.30	0.06	17	1.1	15	28	0.1	64	AS7-5457a
M-07-27	G36312	334	336	0.12	0.07	20	0.5	0.1	30	0.1	64	AS7-5457a
M-07-27	G36313	336	338	0.14	0.07	41	0.7	0.1	36	5	103	AS7-5457a
M-07-27	G36314	338	340	0.21	0.10	42	1	20	54	0.1	72	AS7-5457a
M-07-27	G36315	340	342	0.14	0.07	27	0.5	25	30	5	69	AS7-5457a
M-07-27	G36316	342	344	0.23	0.08	39	0.6	15	30	0.1	67	AS7-5457a
M-07-27	G36317	344	346	0.12	0.06	21	0.9	10	34	0.1	72	AS7-5457a
M-07-27	G36318	346	348	0.64	0.12	18	1.3	30	930	0.1	696	AS7-5457a
M-07-27	G36320	348	350	0.26	0.09	43	1.1	20	214	0.1	288	AS7-5457a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-27	G36321	350	352	0.16	0.05	29	0.7	15	38	0.1	85	AS7-5457a
M-07-27	G36322	352	354	0.14	0.05	27	0.5	20	70	0.1	98	AS7-5457a
M-07-27	G36323	354	356	0.20	0.13	25	1.3	10	48	0.1	71	AS7-5457a
M-07-28	G36324	5.18	6.8	0.62	0.11	50	1.2	20	94	10	239	AS7-5457a
M-07-28	G36325	6.8	8.4	1.09	0.17	60	3.2	20	172	0.1	334	AS7-5457a
M-07-28	G36326	8.4	10	0.56	0.22	9	1.7	40	28	0.1	69	AS7-5460a
M-07-28	G36327	10	12	0.53	0.22	6	2.1	50	32	0.1	53	AS7-5460a
M-07-28	G36328	12	14	1.54	0.26	13	1.7	25	42	0.1	271	AS7-5460a
M-07-28	G36329	14	16	1.21	0.21	20	1.1	30	28	0.1	123	AS7-5460a
M-07-28	G36330	16	18	0.97	0.19	14	1.1	25	36	0.1	72	AS7-5460a
M-07-28	G36331	18	20	0.80	0.21	19	0.9	30	34	0.1	390	AS7-5460a
M-07-28	G36332	20	22	0.56	0.13	73	0.7	35	24	0.1	104	AS7-5460a
M-07-28	G36333	22	24.1	0.78	0.17	34	0.9	40	28	0.1	160	AS7-5460a
M-07-28	G36334	24.9	25.3	0.08	0.02	17	0.3	110	178	0.1	601	AS7-5460a
M-07-28	G36335	25.3	25.8	0.63	0.15	17	1.9	90	76	45	207	AS7-5460a
M-07-28	G36336	26.6	28	0.71	0.16	11	1.5	30	66	0.1	198	AS7-5460a
M-07-28	G36337	28	30	0.75	0.16	14	1.1	35	104	0.1	326	AS7-5460a
M-07-28	G36338	30	32	0.87	0.20	16	1.1	10	30	0.1	80	AS7-5460a
M-07-28	G36339	32	34	1.02	0.19	18	1.2	35	36	0.1	101	AS7-5460a
M-07-28	G36340	34	36	1.21	0.22	14	1	25	48	0.1	851	AS7-5460a
M-07-28	G36341	36	38	1.20	0.23	14	1.3	25	58	0.1	117	AS7-5460a
M-07-28	G36342	38	40	1.08	0.22	12	1.2	45	38	0.1	30	AS7-5460a
M-07-28	G36343	40	42	0.83	0.21	14	1.4	40	40	0.1	27	AS7-5460a
M-07-28	G36344	42	44	0.71	0.18	14	0.9	35	42	0.1	16	AS7-5460a
M-07-28	G36345	44	46	1.16	0.23	16	1.3	20	38	0.1	90	AS7-5460a
M-07-28	G36346	46	48	0.87	0.21	11	1	10	52	0.1	96	AS7-5460a
M-07-28	G36347	48	50	0.79	0.18	20	1.3	15	42	0.1	42	AS7-5460a
M-07-28	G36348	50	52	0.99	0.17	15	1	35	36	0.1	141	AS7-5460a
M-07-28	G36349	52	54	0.82	0.21	18	1.5	25	60	0.1	164	AS7-5460a
M-07-28	G36350	54	56	0.90	0.18	29	1	30	58	0.1	85	AS7-5460a
M-07-28	G36351	56	58	1.06	0.19	21	1	35	32	0.1	28	AS7-5460a
M-07-28	G36352	58	60	1.12	0.17	24	0.7	40	34	0.1	92	AS7-5460a
M-07-28	G36353	60	62	1.15	0.23	41	1.1	50	38	0.1	82	AS7-5460a
M-07-28	G36354	62	64	0.93	0.18	31	1.2	20	32	0.1	80	AS7-5460a
M-07-28	G36355	64	66	0.72	0.22	25	1.1	30	30	0.1	1182	AS7-5460a
M-07-28	G36357	66	68	0.83	0.16	24	0.9	25	32	0.1	56	AS7-5460a
M-07-28	G36359	68	70	0.62	0.16	20	1.1	25	30	0.1	379	AS7-5460a
M-07-28	G36360	70	72	0.61	0.12	23	0.8	30	28	0.1	71	AS7-5460a
M-07-28	G36361	72	73.6	0.64	0.15	39	1.3	0.1	34	0.1	150	AS7-5458a
M-07-28	G36362	74.37	76	0.80	0.17	23	2.2	0.1	56	0.1	338	AS7-5458a
M-07-28	G36363	76	78	0.88	0.21	17	1.7	0.1	28	0.1	61	AS7-5458a
M-07-28	G36364	78	80	0.71	0.18	82	1.6	0.1	36	0.1	42	AS7-5458a
M-07-28	G36365	80	82	0.53	0.22	21	2	0.1	26	0.1	29	AS7-5458a
M-07-28	G36366	82	84	0.97	0.18	26	1.3	0.1	26	0.1	20	AS7-5458a
M-07-28	G36367	84	86	0.90	0.20	23	1.4	0.1	30	0.1	107	AS7-5458a
M-07-28	G36368	86	88	0.81	0.18	37	1.1	20	32	0.1	14	AS7-5458a
M-07-28	G36369	88	90	1.07	0.17	11	1	0.1	26	0.1	13	AS7-5458a
M-07-28	G36370	90	92	1.18	0.22	24	1.3	5	36	0.1	27	AS7-5458a
M-07-28	G36372	92	94	0.82	0.25	21	1	0.1	30	0.1	32	AS7-5458a
M-07-28	G36373	94	96	1.28	0.28	22	1.3	0.1	24	0.1	14	AS7-5458a
M-07-28	G36374	96	98	0.74	0.20	24	0.8	5	32	0.1	17	AS7-5458a
M-07-28	G36375	98	100	0.64	0.22	74	1.4	15	22	10	21	AS7-5458a
M-07-28	G36376	100	102	0.91	0.16	34	0.9	0.1	22	0.1	9	AS7-5458a
M-07-28	G36377	102	104	0.74	0.15	74	1.2	45	24	20	26	AS7-5458a
M-07-28	G36378	104	106	0.99	0.18	67	1.4	85	26	60	48	AS7-5458a
M-07-28	G36379	106	108	0.42	0.16	52	0.8	55	14	40	30	AS7-5458a
M-07-28	G36381	108	110	0.61	0.14	38	1	55	16	70	39	AS7-5458a
M-07-28	G36382	110	112	0.86	0.14	61	0.7	45	30	35	22	AS7-5458a
M-07-28	G36383	112	114	0.97	0.16	68	0.7	25	26	25	20	AS7-5458a
M-07-28	G36384	114	116	0.52	0.12	105	0.8	15	34	20	17	AS7-5458a
M-07-28	G36385	116	118	0.69	0.16	73	0.6	5	26	0.1	32	AS7-5458a
M-07-28	G36386	118	120	0.62	0.13	93	0.7	0.1	34	5	14	AS7-5458a
M-07-28	G36387	120	122	0.56	0.12	46	1.6	25	28	45	28	AS7-5458a
M-07-28	G36388	122	124	0.86	0.16	46	2.3	20	20	40	35	AS7-5458a
M-07-28	G36390	124	126	0.80	0.15	77	1.4	0.1	18	0.1	21	AS7-5458a
M-07-28	G36391	126	128	0.62	0.12	63	1.2	15	18	0.1	27	AS7-5458a
M-07-28	G36392	128	130	0.80	0.18	52	1.6	20	24	0.1	27	AS7-5458a
M-07-28	G36393	130	132	0.78	0.13	71	1.3	20	20	0.1	13	AS7-5458a
M-07-28	G36394	132	134	2.04	0.14	74	27.7	135	336	35	1542	AS7-5458a
M-07-28	G36395	134	136	1.19	0.14	49	5.8	15	32	0.1	292	AS7-5458a
M-07-28	G36396	136	138	1.76	0.17	93	5.7	40	56	0.1	161	AS7-5464a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-28	G36397	138	140	0.95	0.22	58	3.2	10	46	0.1	86	AS7-5464a
M-07-28	G36398	140	142	0.79	0.16	49	2.3	30	30	5	124	AS7-5464a
M-07-28	G36399	142	144	0.74	0.15	63	1.8	0.1	26	0.1	65	AS7-5464a
M-07-28	G36400	144	146	0.94	0.15	81	1.6	0.1	24	0.1	21	AS7-5464a
M-07-28	G36401	146	148	0.72	0.15	56	1.4	5	20	0.1	90	AS7-5464a
M-07-28	G36402	148	150	0.72	0.17	40	3.1	0.1	20	0.1	292	AS7-5464a
M-07-28	G36403	150	152	0.77	0.14	67	2.1	0.1	52	0.1	578	AS7-5464a
M-07-28	G36404	152	154	0.79	0.17	80	1.8	0.1	46	0.1	236	AS7-5464a
M-07-28	G36405	154	156	0.81	0.14	64	1.9	25	28	0.1	505	AS7-5464a
M-07-28	G36406	156	158	0.81	0.19	90	2.5	25	18	5	173	AS7-5464a
M-07-28	G36407	158	160	1.07	0.13	64	1.1	0.1	22	0.1	178	AS7-5464a
M-07-28	G36409	160	162	1.34	0.29	108	1.9	0.1	20	0.1	199	AS7-5464a
M-07-28	G36410	162	164	0.78	0.16	92	1.5	10	28	0.1	76	AS7-5464a
M-07-28	G36411	164	166	1.75	0.28	85	2.1	10	234	0.1	818	AS7-5464a
M-07-28	G36412	166	168	0.86	0.21	103	1.4	0.1	134	0.1	788	AS7-5464a
M-07-28	G36414	168	170	1.06	0.31	860	1.2	15	70	0.1	223	AS7-5464a
M-07-28	G36415	170	172	0.68	0.21	179	1.4	45	58	15	548	AS7-5464a
M-07-28	G36416	172	174	0.62	0.24	90	1	15	22	0.1	441	AS7-5464a
M-07-28	G36417	174	176	1.08	0.20	128	1.2	5	24	0.1	140	AS7-5464a
M-07-28	G36418	176	178	1.02	0.18	169	1.3	20	42	0.1	101	AS7-5464a
M-07-28	G36419	178	180	0.81	0.13	179	1	15	26	0.1	133	AS7-5464a
M-07-28	G36420	180	182	0.71	0.14	128	0.9	0.1	26	0.1	227	AS7-5464a
M-07-28	G36421	182	184	0.79	0.13	109	1.9	35	32	5	273	AS7-5464a
M-07-28	G36422	184	186	0.75	0.18	246	1.1	0.1	84	0.1	211	AS7-5464a
M-07-28	G36423	186	188	1.09	0.14	134	1.1	15	30	0.1	42	AS7-5464a
M-07-28	G36424	188	190	0.81	0.17	70	0.9	0.1	194	0.1	218	AS7-5464a
M-07-28	G36425	190	192	0.66	0.16	108	1.8	10	132	0.1	226	AS7-5464a
M-07-28	G36427	192	194	0.66	0.26	30	2.4	0.1	36	0.1	43	AS7-5464a
M-07-28	G36428	194	196	1.30	0.23	45	1.6	0.1	30	0.1	108	AS7-5464a
M-07-28	G36429	196	198	1.11	0.20	92	1.5	0.1	40	0.1	33	AS7-5464a
M-07-28	G36430	198	200	0.67	0.19	93	1.5	0.1	38	0.1	50	AS7-5464a
M-07-28	G36431	200	201.35	0.42	0.19	55	1.7	0.1	50	0.1	39	AS7-5465a
M-07-28	G36432	201.35	203	0.52	0.21	136	1.8	0.1	44	0.1	55	AS7-5465a
M-07-28	G36433	203	205	0.82	0.19	55	2.3	0.1	62	0.1	84	AS7-5465a
M-07-28	G36434	205	207	0.49	0.18	104	2.4	5	102	0.1	161	AS7-5465a
M-07-28	G36435	207	209	0.62	0.19	51	1.7	0.1	70	0.1	118	AS7-5465a
M-07-28	G36436	209	211	0.89	0.15	45	1.5	0.1	36	0.1	88	AS7-5465a
M-07-28	G36437	211	213.14	0.70	0.15	45	2.2	40	94	0.1	220	AS7-5465a
M-07-28	G36438	213.14	215	0.34	0.15	146	2.9	35	80	0.1	121	AS7-5465a
M-07-28	G36440	215	217	0.40	0.20	62	2.7	10	54	0.1	105	AS7-5465a
M-07-28	G36441	217	219	0.28	0.16	45	2.4	0.1	62	0.1	130	AS7-5465a
M-07-28	G36442	219	221	0.33	0.17	107	2.5	0.1	70	0.1	117	AS7-5465a
M-07-28	G36443	221	223	0.27	0.13	132	2.1	0.1	128	0.1	194	AS7-5465a
M-07-28	G36444	223	225	0.25	0.13	61	0.8	0.1	74	0.1	69	AS7-5465a
M-07-28	G36445	225	227	0.60	0.16	77	1.2	0.1	56	0.1	48	AS7-5465a
M-07-28	G36446	227	229	0.49	0.17	76	1.7	0.1	52	0.1	50	AS7-5465a
M-07-28	G36447	229	231.25	0.27	0.11	104	1.3	0.1	30	0.1	57	AS7-5465a
M-07-28	G36449	231.25	233	0.29	0.11	61	1.4	0.1	34	0.1	38	AS7-5465a
M-07-28	G36450	233	235	0.37	0.15	82	1.7	0.1	46	0.1	33	AS7-5465a
M-07-28	G36451	235	237	0.28	0.10	59	1.3	0.1	48	0.1	58	AS7-5465a
M-07-28	G36453	237	239	0.24	0.08	52	1.2	5	40	0.1	78	AS7-5465a
M-07-28	G36454	239	241	0.16	0.07	26	1.2	0.1	34	5	125	AS7-5465a
M-07-28	G36455	241	243	0.29	0.09	49	1.4	0.1	22	0.1	49	AS7-5465a
M-07-28	G36456	243	245	0.28	0.07	60	2.2	0.1	18	0.1	39	AS7-5465a
M-07-28	G36457	245	247	0.57	0.12	54	5.6	0.1	54	0.1	40	AS7-5465a
M-07-28	G36458	247	249	0.57	0.10	111	17.1	60	94	30	244	AS7-5465a
M-07-28	G36459	249	251	0.47	0.09	54	12.1	80	48	35	156	AS7-5465a
M-07-28	G36460	251	253	0.51	0.09	68	4.1	30	38	20	314	AS7-5465a
M-07-28	G36461	253	255	0.16	0.05	113	4	75	34	25	52	AS7-5465a
M-07-28	G36462	255	257	0.24	0.07	74	6.2	95	56	30	90	AS7-5465a
M-07-28	G36463	257	259	0.27	0.08	92	2.1	15	26	5	156	AS7-5465a
M-07-28	G36464	259	261	0.49	0.10	24	4.3	0.1	58	0.1	55	AS7-5465a
M-07-28	G36465	261	263	0.32	0.10	66	2.7	0.1	52	0.1	70	AS7-5465a
M-07-28	G36466	263	265	0.40	0.10	97	7.4	55	66	25	202	AS7-5467a
M-07-28	G36467	265	267	0.87	0.10	48	6.4	10	124	0.1	163	AS7-5467a
M-07-28	G36468	267	269	0.25	0.09	67	3.2	5	44	0.1	131	AS7-5467a
M-07-28	G36469	269	271	0.47	0.08	100	2.3	20	40	10	127	AS7-5467a
M-07-28	G36470	271	273	0.50	0.07	150	6.1	10	38	0.1	86	AS7-5467a
M-07-28	G36471	273	275	0.34	0.04	108	6.9	15	112	0.1	82	AS7-5467a
M-07-28	G36472	275	277	0.24	0.12	35	2.7	10	66	10	134	AS7-5467a
M-07-28	G36473	277	279	0.33	0.11	42	1.3	0.1	58	5	52	AS7-5467a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-28	G36474	279	281	0.35	0.09	56	0.8	0.1	42	5	47	AS7-5467a
M-07-28	G36475	281	283	0.39	0.09	53	0.8	5	56	15	53	AS7-5467a
M-07-28	G36476	283	285	0.24	0.09	39	0.8	0.1	46	10	65	AS7-5467a
M-07-28	G36477	285	287	0.23	0.08	67	0.6	0.1	36	0.1	50	AS7-5467a
M-07-28	G36478	287	289	0.28	0.09	42	0.8	5	62	0.1	68	AS7-5467a
M-07-28	G36479	289	291	0.24	0.13	43	1.3	25	78	25	138	AS7-5467a
M-07-28	G36480	291	293	0.43	0.11	93	1.2	0.1	64	10	38	AS7-5467a
M-07-28	G36481	293	295	0.31	0.07	47	0.9	0.1	74	5	162	AS7-5467a
M-07-28	G36482	295	297	0.27	0.08	114	0.6	20	86	25	167	AS7-5467a
M-07-28	G36484	297	299	0.80	0.12	38	2.1	240	230	160	1025	AS7-5467a
M-07-28	G36485	299	301	0.74	0.04	114	0.8	45	58	45	115	AS7-5467a
M-07-28	G36486	301	303	0.30	0.05	149	0.4	30	44	25	69	AS7-5467a
M-07-28	G36487	303	305	0.23	0.05	106	0.5	25	42	0.1	87	AS7-5467a
M-07-28	G36488	305	307	0.43	0.20	164	1	20	56	30	238	AS7-5467a
M-07-28	G36490	307	309	0.15	0.06	87	3.2	80	66	115	112	AS7-5467a
M-07-28	G36491	309	311	0.17	0.06	207	0.8	30	54	25	89	AS7-5467a
M-07-28	G36492	311	312.5	0.21	0.08	156	1.3	35	36	20	53	AS7-5467a
M-07-28	G36493	312.5	313.7	0.29	0.09	175	1.6	30	38	35	53	AS7-5467a
M-07-28	G36494	313.7	315	0.12	0.07	111	1.4	10	48	10	59	AS7-5467a
M-07-28	G36495	315	317	0.34	0.12	86	1.2	0.1	42	10	82	AS7-5467a
M-07-28	G36496	317	319	0.18	0.08	65	0.8	0.1	52	0.1	69	AS7-5467a
M-07-28	G36497	319	321	0.17	0.08	93	0.7	0.1	56	15	88	AS7-5467a
M-07-28	G36498	321	323	0.28	0.11	101	0.9	0.1	40	10	83	AS7-5467a
M-07-28	G36499	323	325	0.23	0.05	121	0.5	0.1	102	10	142	AS7-5467a
M-07-28	G36500	325	327	0.32	0.07	172	0.5	5	52	10	69	AS7-5467a
M-07-28	G36501	327	329	0.16	0.09	150	0.8	15	58	0.1	42	AS7-5474a
M-07-28	G36502	329	331	0.19	0.09	85	0.9	15	36	0.1	37	AS7-5474a
M-07-28	G36503	331	333	0.16	0.08	72	0.8	15	52	5	68	AS7-5474a
M-07-28	G36505	333	335	0.14	0.07	202	0.6	20	38	10	35	AS7-5474a
M-07-28	G36506	335	337	0.13	0.08	56	0.5	10	42	10	42	AS7-5474a
M-07-28	G36507	337	339	0.14	0.06	113	0.4	30	52	5	86	AS7-5474a
M-07-28	G36509	339	341	0.19	0.09	518	0.6	25	42	5	53	AS7-5474a
M-07-28	G36510	341	343	0.21	0.08	71	0.5	25	36	10	45	AS7-5474a
M-07-28	G36511	343	345	0.15	0.09	79	0.6	0.1	38	15	35	AS7-5474a
M-07-28	G36512	345	347	0.17	0.06	56	0.5	25	34	15	39	AS7-5474a
M-07-28	G36513	347	349	0.17	0.06	45	0.4	15	38	0.1	36	AS7-5474a
M-07-28	G36514	349	351	0.18	0.07	104	0.6	25	34	5	46	AS7-5474a
M-07-28	G36515	351	353	0.26	0.10	180	0.8	25	48	10	38	AS7-5474a
M-07-28	G36516	353	355	0.19	0.07	38	1.2	15	46	10	71	AS7-5474a
M-07-28	G36517	355	357	0.59	0.06	62	3.6	30	42	0.1	41	AS7-5474a
M-07-28	G36518	357	359	0.13	0.06	125	1.5	45	38	10	44	AS7-5474a
M-07-28	G36520	359	361	0.13	0.03	43	0.7	25	34	5	46	AS7-5474a
M-07-28	G36521	361	363	0.08	0.04	20	0.7	30	36	5	37	AS7-5474a
M-07-28	G36522	363	365	0.41	0.04	24	1	25	32	25	50	AS7-5474a
M-07-28	G36523	365	367	0.17	0.04	44	1.9	40	34	5	42	AS7-5474a
M-07-28	G36524	367	369	0.35	0.03	23	0.8	35	30	5	32	AS7-5474a
M-07-28	G36525	369	370.8	0.13	0.04	60	1.5	60	32	5	32	AS7-5474a
M-07-28	G36526	370.8	373	0.19	0.05	30	1.3	25	34	5	45	AS7-5474a
M-07-28	G36527	373	375	0.13	0.06	43	1.9	15	40	10	59	AS7-5474a
M-07-28	G36528	375	377	0.14	0.05	39	1.7	50	32	5	40	AS7-5474a
M-07-28	G36529	377	379	0.13	0.05	42	1.8	45	70	0.1	73	AS7-5474a
M-07-28	G36530	379	381	0.19	0.06	53	2.3	35	50	10	55	AS7-5474a
M-07-28	G36531	381	383	0.13	0.06	116	1.5	30	48	15	42	AS7-5474a
M-07-28	G36532	383	385	0.15	0.06	46	1.3	40	68	10	30	AS7-5474a
M-07-28	G36533	385	387	0.94	0.05	128	2	60	68	25	39	AS7-5474a
M-07-28	G36534	387	389	0.19	0.05	60	1.5	60	70	0.1	41	AS7-5474a
M-07-28	G36535	389	391	0.21	0.06	57	1.2	25	52	10	40	AS7-5474a
M-07-28	G36536	391	393	0.23	0.05	42	1.3	0.1	34	15	35	AS7-5477a
M-07-28	G36537	393	395	0.13	0.03	18	0.9	0.1	28	10	36	AS7-5477a
M-07-28	G36538	395	397	0.15	0.04	22	1.1	0.1	32	0.1	22	AS7-5477a
M-07-28	G36539	397	398.37	0.20	0.06	11	1.5	0.1	38	20	27	AS7-5477a
M-07-29	G34368	6.7	8	1.18	0.26	31	4	45	38	0.1	40	AS7-5459a
M-07-29	G34369	8	9.4	1.07	0.20	33	2.7	25	46	0.1	90	AS7-5459a
M-07-29	G34370	9.4	11.4	0.79	0.25	41	3.3	35	42	0.1	91	AS7-5459a
M-07-29	G34371	11.4	13.4	1.11	0.26	25	4.1	35	44	0.1	62	AS7-5459a
M-07-29	G34373	13.4	15	1.17	0.28	19	4.9	60	54	0.1	73	AS7-5459a
M-07-29	G34374	15	17	0.69	0.20	14	3	25	38	0.1	97	AS7-5459a
M-07-29	G34375	17	19	0.87	0.17	17	2.9	85	52	0.1	110	AS7-5459a
M-07-29	G34376	19	20.5	1.07	0.28	16	4.7	5	46	0.1	92	AS7-5466a
M-07-29	G34377	20.5	21.9	1.02	0.26	23	4.4	15	26	0.1	53	AS7-5466a
M-07-29	G34378	21.9	23	0.52	0.23	14	3.7	15	20	0.1	44	AS7-5466a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-29	G34379	23	25	0.95	0.23	19	4.6	35	26	0.1	31	AS7-5466a
M-07-29	G34380	25	27	0.83	0.19	22	4	45	22	0.1	16	AS7-5466a
M-07-29	G34382	27	29	1.43	0.33	24	6.1	35	32	0.1	61	AS7-5466a
M-07-29	G34383	29	31	0.75	0.25	17	3.9	10	20	0.1	43	AS7-5466a
M-07-29	G34384	31	32.45	0.92	0.23	19	3.8	20	24	0.1	68	AS7-5466a
M-07-29	G34385	32.45	34	1.28	0.24	16	5	45	18	0.1	25	AS7-5466a
M-07-29	G34386	34	36	1.01	0.22	18	5.3	50	26	0.1	35	AS7-5466a
M-07-29	G34387	36	38	1.49	0.33	19	7.1	40	38	0.1	22	AS7-5466a
M-07-29	G34388	38	40	1.55	0.24	16	6.5	45	40	0.1	17	AS7-5466a
M-07-29	G34389	40	42	1.06	0.27	13	4.7	10	24	0.1	71	AS7-5466a
M-07-29	G34390	42	44	0.97	0.32	16	5.9	15	32	0.1	59	AS7-5466a
M-07-29	G34391	44	46.1	0.76	0.23	17	4.5	25	32	0.1	42	AS7-5466a
M-07-29	G34392	46.1	48	0.05	0.00	5	0.5	10	54	5	135	AS7-5466a
M-07-29	G34394	48	50	0.00	0.01	8	0.7	5	52	10	123	AS7-5466a
M-07-29	G34395	50	52	0.18	0.01	5	1.6	20	52	0.1	107	AS7-5466a
M-07-29	G34396	52	53.3	0.22	0.01	6	1.9	70	60	5	151	AS7-5466a
M-07-29	G34397	53.3	55	0.99	0.34	19	7.3	55	60	0.1	19	AS7-5466a
M-07-29	G34398	55	57	1.12	0.33	24	5.5	10	26	0.1	49	AS7-5466a
M-07-29	G34399	57	59	0.90	0.27	23	4.1	10	34	0.1	62	AS7-5466a
M-07-29	G34400	59	61	3.60	0.30	30	6.9	45	34	0.1	25	AS7-5466a
M-07-29	G34401	61	63	0.65	0.24	21	3.7	20	36	0.1	73	AS7-5466a
M-07-29	G34402	63	65	11.30	0.20	10	8.3	0.1	40	0.1	24	AS7-5466a
M-07-29	G34403	65	67	2.60	0.39	13	5.9	20	34	0.1	14	AS7-5466a
M-07-29	G34405	67	69	1.48	0.42	21	5.8	10	20	0.1	32	AS7-5466a
M-07-29	G34406	69	71	0.80	0.27	27	4.2	5	32	0.1	23	AS7-5466a
M-07-29	G34407	71	73	4.10	0.31	15	5.9	55	38	0.1	26	AS7-5466a
M-07-29	G34408	73	75	1.02	0.42	19	6.2	20	22	0.1	48	AS7-5466a
M-07-29	G34409	75	77	1.05	0.36	19	4.5	20	26	0.1	32	AS7-5466a
M-07-29	G34410	77	79	0.67	0.19	24	2.4	10	26	0.1	80	AS7-5466a
M-07-29	G34411	79	81	0.84	0.34	25	4.2	0.1	34	0.1	51	AS7-5468a
M-07-29	G34412	81	83	0.67	0.31	21	3.1	0.1	26	0.1	59	AS7-5468a
M-07-29	G34413	83	85	1.43	0.31	23	4.2	40	36	0.1	22	AS7-5468a
M-07-29	G34414	85	87	1.09	0.33	19	3.6	15	34	0.1	50	AS7-5468a
M-07-29	G34416	87	89	0.61	0.24	32	2.5	10	34	0.1	104	AS7-5468a
M-07-29	G34417	89	91	0.78	0.29	29	3.2	5	26	0.1	54	AS7-5468a
M-07-29	G34418	91	93	0.96	0.28	22	3.7	15	42	0.1	61	AS7-5468a
M-07-29	G34419	93	95	0.76	0.31	17	3.2	10	32	0.1	55	AS7-5468a
M-07-29	G34420	95	97	1.10	0.37	31	3.9	35	48	0.1	33	AS7-5468a
M-07-29	G34421	97	99	0.92	0.23	26	3.6	90	34	10	33	AS7-5468a
M-07-29	G34422	99	101	0.82	0.27	16	3.5	20	28	0.1	41	AS7-5468a
M-07-29	G34423	101	103	0.80	0.26	20	3.2	0.1	34	0.1	85	AS7-5468a
M-07-29	G34424	103	105	0.86	0.31	18	4.1	20	50	0.1	66	AS7-5468a
M-07-29	G34425	105	107	0.92	0.26	21	4.8	30	34	0.1	52	AS7-5468a
M-07-29	G34427	107	109	0.65	0.20	17	2.7	20	34	0.1	59	AS7-5468a
M-07-29	G34428	109	111	0.78	0.26	23	3.9	35	42	0.1	62	AS7-5468a
M-07-29	G34429	111	113	1.16	0.27	15	3.2	30	36	0.1	23	AS7-5468a
M-07-29	G34430	113	115	0.93	0.26	20	2.5	15	42	10	79	AS7-5468a
M-07-29	G34431	115	117	1.61	0.30	20	3.1	25	30	0.1	38	AS7-5468a
M-07-29	G34432	117	118.75	1.49	0.28	18	2.8	40	30	10	54	AS7-5468a
M-07-29	G34433	118.75	120	0.60	0.17	18	1.8	20	44	0.1	56	AS7-5468a
M-07-29	G34435	120	122	0.75	0.19	20	2.5	20	46	0.1	91	AS7-5468a
M-07-29	G34436	122	124	0.87	0.29	21	3.3	25	48	0.1	47	AS7-5468a
M-07-29	G34437	124	126	1.35	0.42	19	3.8	15	36	0.1	45	AS7-5468a
M-07-29	G34438	126	128	1.24	0.26	15	3.1	65	40	0.1	57	AS7-5468a
M-07-29	G34439	128	130	0.88	0.29	20	3.4	30	42	0.1	56	AS7-5468a
M-07-29	G34440	130	132	0.76	0.22	23	4	60	46	0.1	63	AS7-5468a
M-07-29	G34441	132	133	1.46	0.36	18	4.3	20	30	0.1	64	AS7-5468a
M-07-29	G34442	133	134	1.22	0.19	42	2.2	55	32	0.1	77	AS7-5468a
M-07-29	G34443	134	136	0.93	0.20	27	2.3	45	30	15	82	AS7-5468a
M-07-29	G34444	136	138	0.48	0.15	16	2.4	20	28	0.1	73	AS7-5468a
M-07-29	G34445	138	140	1.36	0.36	28	4.6	5	30	0.1	53	AS7-5468a
M-07-29	G34446	140	142	0.35	0.13	20	2	10	28	0.1	53	AS7-5472a
M-07-29	G34447	142	144	0.67	0.20	15	3	10	30	0.1	58	AS7-5472a
M-07-29	G34448	144	146	0.68	0.18	23	2.2	10	30	10	50	AS7-5472a
M-07-29	G34449	146	148	0.44	0.13	15	1.7	10	22	5	47	AS7-5472a
M-07-29	G34450	148	149.65	0.74	0.21	13	2.5	0.1	20	0.1	47	AS7-5472a
M-07-29	G34451	149.65	151	0.46	0.13	13	1.4	0.1	26	0.1	48	AS7-5472a
M-07-29	G34452	151	153	0.84	0.21	18	2.5	0.1	26	0.1	49	AS7-5472a
M-07-29	G34453	153	155	0.61	0.22	21	2.2	15	26	15	49	AS7-5472a
M-07-29	G34454	155	157	0.30	0.10	12	1	5	22	0.1	45	AS7-5472a
M-07-29	G34455	157	159	0.70	0.16	17	1.6	15	30	0.1	50	AS7-5472a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-29	G34456	159	161	1.06	0.23	14	2.3	10	34	0.1	50	AS7-5472a
M-07-29	G34457	161	162.4	0.39	0.12	17	1.2	10	24	0.1	64	AS7-5472a
M-07-29	G34458	162.4	163.8	0.44	0.14	17	1.6	0.1	20	0.1	58	AS7-5472a
M-07-29	G34459	163.8	165	0.25	0.09	13	0.8	5	18	5	43	AS7-5472a
M-07-29	G34461	165	167	0.36	0.15	13	1.7	10	20	5	97	AS7-5472a
M-07-29	G34462	167	169	0.30	0.09	20	1.1	40	26	5	62	AS7-5472a
M-07-29	G34463	169	171	0.35	0.10	14	1.1	0.1	20	0.1	39	AS7-5472a
M-07-29	G34464	171	173	0.33	0.11	12	1.2	15	22	0.1	41	AS7-5472a
M-07-29	G34465	173	175	0.23	0.09	12	0.8	5	24	0.1	48	AS7-5472a
M-07-29	G34466	175	177	0.55	0.21	10	2	20	24	0.1	60	AS7-5472a
M-07-29	G34467	177	179	0.64	0.37	17	3.1	15	26	5	52	AS7-5472a
M-07-29	G34468	179	181	0.60	0.20	12	2	20	28	0.1	53	AS7-5472a
M-07-29	G34469	181	183	0.63	0.14	17	1.9	10	32	10	60	AS7-5472a
M-07-29	G34470	183	185	0.35	0.15	16	11.9	0.1	48	0.1	71	AS7-5472a
M-07-29	G34471	185	187.15	0.84	0.24	20	21.1	25	1014	10	1160	AS7-5472a
M-07-29	G34472	187.15	189	0.66	0.18	17	3.2	10	24	5	49	AS7-5472a
M-07-29	G34473	189	191	0.43	0.16	11	1.6	10	30	5	82	AS7-5472a
M-07-29	G34475	191	193	0.19	0.07	13	0.7	10	24	5	55	AS7-5472a
M-07-29	G34476	193	195	0.43	0.24	11	2.3	35	30	0.1	32	AS7-5472a
M-07-29	G34477	195	197	0.53	0.13	13	1.5	20	26	10	48	AS7-5472a
M-07-29	G34478	197	198.2	0.58	0.13	11	1.9	15	28	0.1	41	AS7-5472a
M-07-29	G34479	198.2	199.35	0.31	0.07	13	1	10	26	0.1	45	AS7-5472a
M-07-29	G34480	199.35	201	0.24	0.07	18	0.8	25	24	0.1	59	AS7-5472a
M-07-29	G34481	201	203	0.24	0.07	14	0.9	25	36	0.1	65	AS7-5473a
M-07-29	G34482	203	205	0.22	0.09	21	0.9	20	22	0.1	50	AS7-5473a
M-07-29	G34483	205	207	0.17	0.08	14	0.8	10	28	0.1	56	AS7-5473a
M-07-29	G34484	207	209	0.10	0.05	17	0.4	10	24	15	67	AS7-5473a
M-07-29	G34485	209	211	0.14	0.08	16	0.7	20	28	0.1	59	AS7-5473a
M-07-29	G34486	211	213	0.16	0.08	13	0.7	10	24	0.1	59	AS7-5473a
M-07-29	G34487	213	215	0.11	0.07	9	0.6	15	22	0.1	50	AS7-5473a
M-07-29	G34489	215	217	0.25	0.09	22	0.9	25	28	0.1	54	AS7-5473a
M-07-29	G34490	217	219	0.35	0.12	11	1.1	20	26	0.1	65	AS7-5473a
M-07-29	G34491	219	221	0.24	0.11	13	1.2	25	28	0.1	39	AS7-5473a
M-07-29	G34492	221	222	0.24	0.08	9	0.9	20	18	0.1	45	AS7-5473a
M-07-29	G34493	222	224	0.29	0.14	12	2.1	40	36	0.1	32	AS7-5473a
M-07-29	G34494	224	226	0.22	0.10	14	2.2	35	24	0.1	45	AS7-5473a
M-07-29	G34495	226	228	0.95	0.17	12	3	20	34	10	33	AS7-5473a
M-07-29	G34496	228	230	0.36	0.08	16	3.1	25	28	5	81	AS7-5473a
M-07-29	G34497	230	232	0.76	0.13	19	7.8	30	176	10	926	AS7-5473a
M-07-29	G34499	232	234	0.83	0.09	9	3.5	40	66	0.1	34	AS7-5473a
M-07-29	G34500	234	236	0.37	0.15	10	3.5	15	24	0.1	80	AS7-5473a
M-07-29	G34501	236	238	0.54	0.16	14	3.9	30	34	10	87	AS7-5473a
M-07-29	G34502	238	240	0.26	0.09	16	1.3	10	26	5	70	AS7-5473a
M-07-29	G34503	240	242	0.14	0.05	10	0.7	25	22	0.1	45	AS7-5473a
M-07-29	G34504	242	244	0.68	0.17	11	1.9	25	30	0.1	49	AS7-5473a
M-07-29	G34505	244	246	0.51	0.21	10	1.9	20	32	0.1	42	AS7-5473a
M-07-29	G34506	246	248	0.34	0.16	13	1.6	20	50	15	56	AS7-5473a
M-07-29	G34507	248	250	0.29	0.11	14	3.3	25	46	0.1	55	AS7-5473a
M-07-29	G34508	250	252	0.43	0.15	12	3.9	30	134	10	132	AS7-5473a
M-07-29	G34510	252	254	0.88	0.30	13	2.9	25	34	10	67	AS7-5473a
M-07-29	G34511	254	256	0.73	0.29	9	3.6	25	28	0.1	49	AS7-5473a
M-07-29	G34512	256	258	0.64	0.13	17	9.1	35	182	5	212	AS7-5473a
M-07-29	G34513	258	260	0.97	0.14	10	4.9	35	70	0.1	80	AS7-5473a
M-07-29	G34514	260	262	0.60	0.11	17	4.7	30	68	0.1	253	AS7-5473a
M-07-29	G34515	262	264	0.60	0.22	13	7.1	30	60	5	139	AS7-5473a
M-07-29	G34516	264	265.3	0.33	0.09	11	2.6	10	62	0.1	75	AS7-5469a
M-07-29	G34517	265.3	267.3	0.00	0.01	8	0.2	45	56	35	61	AS7-5469a
M-07-29	G34518	267.3	269.3	0.00	0.01	5	0.2	55	52	25	45	AS7-5469a
M-07-29	G34519	269.3	271.25	0.00	0.01	9	0.3	35	52	40	49	AS7-5469a
M-07-29	G34520	271.25	273.25	0.54	0.14	23	5.3	15	42	20	71	AS7-5469a
M-07-29	G34521	273.25	275.25	0.90	0.10	21	1.8	10	34	0.1	64	AS7-5469a
M-07-29	G34522	275.25	277.25	0.58	0.20	14	1.7	10	28	5	52	AS7-5469a
M-07-29	G34523	277.25	278.25	2.77	0.13	11	2.4	40	32	0.1	38	AS7-5469a
M-07-29	G34524	278.25	280.25	0.17	0.18	20	1.9	0.1	26	0.1	67	AS7-5469a
M-07-29	G34525	280.25	282.25	0.51	0.54	13	46.4	10	228	5	313	AS7-5469a
M-07-29	G34527	282.25	284.25	0.70	0.11	9	3.2	5	86	0.1	112	AS7-5469a
M-07-29	G34528	284.25	286.25	0.25	0.11	12	1.3	0.1	22	5	62	AS7-5469a
M-07-29	G34529	286.25	288.25	0.43	0.13	20	1.3	0.1	22	0.1	59	AS7-5469a
M-07-29	G34530	288.25	290.25	0.23	0.07	29	0.8	10	20	0.1	40	AS7-5469a
M-07-29	G34531	290.25	292.25	0.58	0.23	32	1.9	20	22	0.1	67	AS7-5469a
M-07-29	G34532	292.25	294.25	0.19	0.09	16	0.8	0.1	20	0.1	47	AS7-5469a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-29	G34533	294.25	296.25	0.15	0.06	162	0.5	0.1	26	0.1	62	AS7-5469a
M-07-29	G34534	296.25	298.25	0.29	0.11	17	1.4	10	22	5	68	AS7-5469a
M-07-29	G34535	298.25	300.35	0.21	0.09	45	1.3	0.1	52	0.1	104	AS7-5469a
M-07-29	G34536	300.35	302.35	1.07	0.10	17	2.2	20	74	5	123	AS7-5469a
M-07-29	G34537	302.35	304.35	0.50	0.13	35	2.7	25	38	15	53	AS7-5469a
M-07-29	G34538	304.35	306.35	0.35	0.30	22	3.3	0.1	38	0.1	75	AS7-5469a
M-07-29	G34539	306.35	308.35	0.34	0.04	30	1.1	20	60	20	292	AS7-5469a
M-07-29	G34541	308.35	310.35	0.22	0.22	74	3.7	20	44	0.1	652	AS7-5469a
M-07-29	G34542	310.35	312.35	0.34	0.11	87	2	25	30	0.1	55	AS7-5469a
M-07-29	G34543	312.35	314.35	0.25	0.07	44	1.1	10	24	0.1	54	AS7-5469a
M-07-29	G34544	314.35	316.35	0.20	0.09	81	1.3	25	50	0.1	49	AS7-5469a
M-07-29	G34545	316.35	318.35	0.29	0.12	96	1.2	20	26	0.1	47	AS7-5469a
M-07-29	G34546	318.35	320.35	0.26	0.10	72	1.6	10	28	0.1	48	AS7-5469a
M-07-29	G34547	320.35	322.35	0.22	0.10	107	4.1	20	32	0.1	55	AS7-5469a
M-07-29	G34548	322.35	324.35	0.18	0.07	38	2.7	25	36	20	64	AS7-5469a
M-07-29	G34549	324.35	326.35	0.31	0.11	101	2.5	25	126	5	72	AS7-5469a
M-07-29	G34550	326.35	328.35	0.18	0.05	40	0.9	10	34	0.1	70	AS7-5469a
M-07-29	G34551	328.35	330.35	0.30	0.09	57	4.3	0.1	202	0.1	1107	AS7-5479a
M-07-29	G34552	330.35	332.35	0.52	0.23	48	2.2	0.1	38	5	75	AS7-5479a
M-07-29	G34553	332.35	334.35	0.27	0.10	76	1	0.1	26	0.1	58	AS7-5479a
M-07-29	G34554	334.35	336.48	0.34	0.06	36	0.9	15	28	0.1	48	AS7-5479a
M-07-30	G36540	3.04	5	0.03	0.00	5	0.3	10	20	10	44	AS7-5477a
M-07-30	G36541	5	7	0.00	0.01	6	0.3	5	20	0.1	60	AS7-5477a
M-07-30	G36542	7	9	0.04	0.01	5	0.2	0.1	14	0.1	57	AS7-5477a
M-07-30	G36543	9	11	0.00	0.02	6	0.2	0.1	6	0.1	71	AS7-5477a
M-07-30	G36544	11	13	0.00	0.04	7	0.3	5	14	0.1	85	AS7-5477a
M-07-30	G36545	13	14.7	0.00	0.06	13	0.4	5	20	0.1	80	AS7-5477a
M-07-30	G36546	17.5	19.5	0.28	0.10	32	3.3	0.1	126	5	53	AS7-5477a
M-07-30	G36547	19.5	21	0.05	0.09	30	2.7	0.1	176	0.1	99	AS7-5477a
M-07-30	G36548	21	23	0.06	0.07	18	4.2	0.1	270	0.1	134	AS7-5477a
M-07-30	G36549	23	25	0.06	0.09	14	2.4	5	98	0.1	106	AS7-5477a
M-07-30	G36550	25	27	0.09	0.13	21	2.5	15	174	5	116	AS7-5477a
M-07-30	G36551	27	28.45	0.11	0.17	27	4	20	202	5	99	AS7-5477a
M-07-30	G36552	28.45	30	0.13	0.12	31	3.4	10	182	0.1	34	AS7-5477a
M-07-30	G36553	30	32	0.50	0.14	29	6.9	25	74	10	43	AS7-5477a
M-07-30	G36555	32	34	0.83	0.78	39	183	470	2604	2775	1505	AS7-5477a
M-07-30	G36556	34	36	0.50	0.36	58	21.7	155	2834	225	5206	AS7-5477a
M-07-30	G36557	36	38	0.20	0.05	10	1.9	10	62	15	33	AS7-5477a
M-07-30	G36558	38	40	1.07	0.05	6	1.6	15	46	10	32	AS7-5477a
M-07-30	G36559	40	42	0.38	0.10	10	2.3	85	60	10	34	AS7-5477a
M-07-30	G36560	42	44	0.36	0.08	9	1	40	36	10	43	AS7-5477a
M-07-30	G36562	44	46	0.42	0.18	8	2.5	60	48	10	55	AS7-5477a
M-07-30	G36563	46	48	0.26	0.09	14	1.8	20	42	15	92	AS7-5477a
M-07-30	G36564	48	50	0.24	0.09	8	1.3	15	44	10	89	AS7-5477a
M-07-30	G36565	50	52	0.13	0.09	7	1.2	35	40	10	67	AS7-5477a
M-07-30	G36566	52	54	0.13	0.04	10	0.8	30	48	10	31	AS7-5477a
M-07-30	G36567	54	56	0.42	0.06	9	0.9	15	30	0.1	36	AS7-5477a
M-07-30	G36568	56	58	0.52	0.13	8	1.4	0.1	26	15	37	AS7-5477a
M-07-30	G36569	58	60	0.36	0.13	8	4.6	0.1	80	10	81	AS7-5477a
M-07-30	G36570	60	62	0.17	0.04	11	1.8	5	52	10	62	AS7-5477a
M-07-30	G36571	62	64	0.34	0.06	8	2.4	10	54	10	77	AS7-5478a
M-07-30	G36572	64	66	0.23	0.10	12	3.2	15	68	5	78	AS7-5478a
M-07-30	G36573	66	68	0.20	0.14	10	2.1	5	26	0.1	46	AS7-5478a
M-07-30	G36574	68	70	0.09	0.05	14	1.5	0.1	20	0.1	36	AS7-5478a
M-07-30	G36575	70	72	0.16	0.04	6	1.7	10	26	0.1	36	AS7-5478a
M-07-30	G36576	72	74	0.39	0.14	14	8.4	10	632	10	1049	AS7-5478a
M-07-30	G36577	74	76	0.13	0.05	11	1.9	0.1	116	0.1	86	AS7-5478a
M-07-30	G36578	76	78	0.09	0.04	8	1.3	0.1	42	0.1	64	AS7-5478a
M-07-30	G36579	78	80	0.21	0.06	7	1.5	0.1	20	5	22	AS7-5478a
M-07-30	G36581	80	82	0.27	0.11	14	1.7	0.1	30	15	35	AS7-5478a
M-07-30	G36582	82	84	0.29	0.09	26	1.8	10	34	0.1	33	AS7-5478a
M-07-30	G36583	84	86	0.90	0.06	18	1.5	10	22	0.1	50	AS7-5478a
M-07-30	G36584	86	88	0.25	0.06	28	1.5	20	32	0.1	33	AS7-5478a
M-07-30	G36585	88	90	0.09	0.04	23	1	0.1	26	0.1	28	AS7-5478a
M-07-30	G36586	90	92	0.14	0.05	15	1.5	0.1	32	0.1	50	AS7-5478a
M-07-30	G36587	92	94	0.11	0.04	14	1.5	0.1	48	5	68	AS7-5478a
M-07-30	G36589	94	96	0.26	0.06	11	1.5	0.1	32	0.1	36	AS7-5478a
M-07-30	G36590	96	98	0.12	0.06	15	1.3	15	58	10	33	AS7-5478a
M-07-30	G36591	98	100	0.36	0.08	18	1.4	0.1	66	5	43	AS7-5478a
M-07-30	G36592	100	102	0.46	0.05	22	1	10	52	15	39	AS7-5478a
M-07-30	G36593	102	104	0.25	0.05	31	1	30	122	10	64	AS7-5478a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-30	G36594	104	106	0.64	0.07	22	0.9	10	86	10	59	AS7-5478a
M-07-30	G36595	106	108	0.34	0.05	10	0.8	15	76	0.1	32	AS7-5478a
M-07-30	G36596	108	110	0.12	0.06	17	0.6	10	74	15	79	AS7-5478a
M-07-30	G36598	110	112	5.85	0.07	31	1.4	20	72	10	54	AS7-5478a
M-07-30	G36599	112	114	0.69	0.04	7	0.9	15	110	10	65	AS7-5478a
M-07-30	G36600	114	116	0.14	0.05	18	2.4	20	408	10	46	AS7-5478a
M-07-30	G36601	116	118	0.41	0.04	63	2.4	70	284	60	46	AS7-5478a
M-07-30	G36602	118	120	0.19	0.02	53	1.9	55	114	60	73	AS7-5478a
M-07-30	G36603	120	122	0.73	0.01	27	2.3	20	50	20	23	AS7-5478a
M-07-30	G36604	122	124	0.35	0.02	24	1.5	15	36	10	140	AS7-5478a
M-07-30	G36605	124	126	0.24	0.13	10	2	30	46	10	65	AS7-5478a
M-07-30	G36606	126	128	0.33	0.06	43	2.6	25	82	0.1	75	AS7-5487a
M-07-30	G36607	128	130	0.16	0.48	46	6.4	150	110	145	120	AS7-5487a
M-07-30	G36608	130	132	0.33	0.18	24	3.4	50	68	20	166	AS7-5487a
M-07-30	G36609	132	134	0.09	0.01	5	0.5	25	16	0.1	15	AS7-5487a
M-07-30	G36610	134	136	0.55	0.02	5	1.3	25	14	10	9	AS7-5487a
M-07-30	G36611	136	138	0.41	0.04	6	2.4	25	20	5	15	AS7-5487a
M-07-30	G36612	138	139.25	0.14	0.02	5	1.1	20	16	0.1	2	AS7-5487a
M-07-30	G36613	139.25	141	0.08	0.01	6	0.4	15	14	0.1	2	AS7-5487a
M-07-30	G36614	141	143	0.44	0.01	4	1.9	45	28	0.1	13	AS7-5487a
M-07-30	G36615	143	145	0.10	0.01	4	0.7	20	24	0.1	24	AS7-5487a
M-07-30	G36617	145	147	0.08	0.01	4	0.7	25	20	0.1	17	AS7-5487a
M-07-30	G36618	147	149	0.10	0.01	5	1	20	30	0.1	21	AS7-5487a
M-07-30	G36619	149	151	0.18	0.01	5	1.6	30	30	0.1	23	AS7-5487a
M-07-30	G36620	151	153	0.21	0.11	7	3.6	35	68	5	86	AS7-5487a
M-07-30	G36621	153	155	0.34	0.02	10	2.2	30	44	15	33	AS7-5487a
M-07-30	G36622	155	157	0.15	0.02	4	1.3	25	28	5	14	AS7-5487a
M-07-30	G36623	157	159	0.10	0.01	5	0.7	25	20	0.1	11	AS7-5487a
M-07-30	G36625	159	161	0.12	0.02	13	1	40	26	0.1	8	AS7-5487a
M-07-30	G36626	161	162.5	0.34	0.07	9	0.8	60	38	10	20	AS7-5487a
M-07-30	G36627	162.5	163.95	0.22	0.06	5	1.6	30	22	5	7	AS7-5487a
M-07-30	G36628	163.95	165	0.20	0.05	6	1.7	40	16	5	5	AS7-5487a
M-07-30	G36629	165	167	0.18	0.04	8	1.1	25	16	0.1	6	AS7-5487a
M-07-30	G36630	167	169	0.26	0.02	8	1.8	50	38	5	30	AS7-5487a
M-07-30	G36631	169	171	0.44	0.07	10	2.7	45	42	0.1	47	AS7-5487a
M-07-30	G36632	171	173	0.20	0.12	17	3.3	45	48	15	45	AS7-5487a
M-07-30	G36633	173	175	0.34	0.31	26	8.5	45	48	5	40	AS7-5487a
M-07-30	G36634	175	177	0.26	0.07	10	3.1	60	32	0.1	20	AS7-5487a
M-07-30	G36635	177	179	0.22	0.03	11	2.4	25	40	0.1	20	AS7-5487a
M-07-30	G36636	179	181	0.11	0.10	4	3.2	20	32	0.1	26	AS7-5487a
M-07-30	G36637	181	183	0.12	0.18	5	3.7	35	46	10	45	AS7-5487a
M-07-30	G36638	183	185	0.07	0.21	5	3.9	25	46	0.1	55	AS7-5487a
M-07-30	G36639	185	187	0.23	0.11	7	2.4	30	40	10	33	AS7-5487a
M-07-30	G36640	187	189	0.08	0.12	3	2.5	30	28	10	25	AS7-5487a
M-07-30	G36641	189	191	0.15	0.12	4	2.6	30	38	5	27	AS7-5484a
M-07-30	G36642	191	193	0.10	0.06	3	1.3	25	30	0.1	21	AS7-5484a
M-07-30	G36643	193	194.46	0.23	0.12	9	2.2	15	36	0.1	43	AS7-5484a
M-07-31	G34555	8.84	11	0.03	0.04	5	0.01	0.1	32	10	69	AS7-5479a
M-07-31	G34556	11	13	0.06	0.15	6	1.1	5	42	0.1	82	AS7-5479a
M-07-31	G34557	13	15	0.05	0.09	4	0.7	0.1	50	0.1	75	AS7-5479a
M-07-31	G34558	15	17	0.08	0.13	8	1.1	15	24	0.1	48	AS7-5479a
M-07-31	G34559	17	19	0.06	0.09	5	0.7	65	20	0.1	39	AS7-5479a
M-07-31	G34560	19	21	0.12	0.19	12	1.5	140	20	10	86	AS7-5479a
M-07-31	G34561	21	23	0.12	0.12	7	1.2	95	28	15	64	AS7-5479a
M-07-31	G34562	23	25	0.25	0.12	10	1.8	40	136	0.1	1135	AS7-5479a
M-07-31	G34563	25	27	0.07	0.12	5	1	5	48	0.1	106	AS7-5479a
M-07-31	G34564	27	29	0.07	0.13	7	0.9	50	30	10	67	AS7-5479a
M-07-31	G34565	29	31	0.12	0.13	8	1	75	60	10	73	AS7-5479a
M-07-31	G34567	31	33	0.06	0.06	5	0.4	10	32	0.1	53	AS7-5479a
M-07-31	G34568	33	35	0.05	0.07	4	0.5	5	34	5	52	AS7-5479a
M-07-31	G34569	35	37	0.07	0.13	6	0.6	10	46	10	100	AS7-5479a
M-07-31	G34570	37	39	0.09	0.09	4	0.5	10	38	0.1	94	AS7-5479a
M-07-31	G34571	39	41	0.26	0.14	42	2.3	95	100	5	109	AS7-5479a
M-07-31	G34572	41	43	0.19	0.11	64	2.3	20	72	20	82	AS7-5479a
M-07-31	G34573	43	45	0.27	0.13	13	2.4	20	36	5	53	AS7-5479a
M-07-31	G34574	45	47	0.64	0.13	7	3.9	30	38	0.1	39	AS7-5479a
M-07-31	G34575	47	49	0.43	0.18	14	5.1	30	52	5	57	AS7-5479a
M-07-31	G34576	49	51	0.28	0.11	9	2.5	30	52	5	48	AS7-5479a
M-07-31	G34577	51	53	0.09	0.15	8	2.5	20	40	5	53	AS7-5479a
M-07-31	G34578	53	55	0.09	0.20	19	4.4	35	218	15	122	AS7-5479a
M-07-31	G34579	55	57	0.21	0.11	36	3.7	25	70	0.1	30	AS7-5479a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-31	G34581	57	58	0.16	0.11	44	3	15	118	5	63	AS7-5479a
M-07-31	G34582	58	60	0.72	0.21	59	2.5	20	20	0.1	34	AS7-5479a
M-07-31	G34583	60	62	1.29	0.33	79	3.6	20	30	15	58	AS7-5479a
M-07-31	G34585	62	64	1.00	0.20	45	2.4	30	34	0.1	54	AS7-5479a
M-07-31	G34586	64	66	0.79	0.25	40	3.4	30	38	0.1	34	AS7-5488a
M-07-31	G34587	66	68	1.45	0.32	27	3.7	35	40	0.1	50	AS7-5488a
M-07-31	G34588	68	70	0.80	0.26	129	2.8	30	48	5	80	AS7-5488a
M-07-31	G34589	70	72	0.33	0.15	46	1.3	20	42	10	88	AS7-5488a
M-07-31	G34591	72	74	0.56	0.19	37	1.8	25	44	0.1	110	AS7-5488a
M-07-31	G34592	74	76	0.13	0.05	16	0.9	50	72	25	175	AS7-5488a
M-07-31	G34593	76	78	1.41	0.30	59	5.1	40	66	10	290	AS7-5488a
M-07-31	G34594	78	80	1.04	0.37	73	10.2	45	78	0.1	153	AS7-5488a
M-07-31	G34595	80	82	0.96	0.28	32	10.2	30	72	0.1	188	AS7-5488a
M-07-31	G34596	82	84	0.90	0.30	20	5.9	25	58	0.1	127	AS7-5488a
M-07-31	G34597	84	86	0.83	0.28	38	2.9	25	42	5	102	AS7-5488a
M-07-31	G34598	86	88	0.88	0.32	35	2.8	15	34	0.1	72	AS7-5488a
M-07-31	G34599	88	90	0.86	0.36	119	3.7	20	34	0.1	34	AS7-5488a
M-07-31	G34601	90	92	0.63	0.22	21	2.3	25	36	0.1	47	AS7-5488a
M-07-31	G34602	92	94	0.49	0.19	35	1.8	20	28	5	58	AS7-5488a
M-07-31	G34603	94	96	0.78	0.19	22	1.9	20	30	0.1	45	AS7-5488a
M-07-31	G34604	96	98	0.86	0.26	40	2.1	30	28	5	48	AS7-5488a
M-07-31	G34605	98	100	0.50	0.14	19	1.3	25	22	10	36	AS7-5488a
M-07-31	G34606	100	102	0.37	0.11	23	1.3	20	24	0.1	36	AS7-5488a
M-07-31	G34607	102	104	0.47	0.15	57	1.5	20	28	5	47	AS7-5488a
M-07-31	G34608	104	106	0.38	0.09	24	1.2	25	26	5	61	AS7-5488a
M-07-31	G34609	106	108	0.33	0.10	20	1.2	15	28	0.1	64	AS7-5488a
M-07-31	G34610	108	110	0.55	0.14	29	1.8	20	34	0.1	52	AS7-5488a
M-07-31	G34611	110	112	0.38	0.12	48	1.5	15	30	5	57	AS7-5488a
M-07-31	G34612	112	114	0.69	0.17	35	2.4	20	30	5	48	AS7-5488a
M-07-31	G34613	114	116	0.41	0.15	40	1.8	25	38	0.1	41	AS7-5488a
M-07-31	G34614	116	118	0.62	0.18	38	2.1	20	28	0.1	37	AS7-5488a
M-07-31	G34615	118	120	0.42	0.13	70	1.6	20	26	0.1	76	AS7-5488a
M-07-31	G34616	120	122	0.62	0.20	37	2.5	20	30	15	83	AS7-5488a
M-07-31	G34617	122	124	1.06	0.24	101	3	15	166	5	62	AS7-5488a
M-07-31	G34618	124	126	1.05	0.31	55	3.6	15	38	0.1	58	AS7-5488a
M-07-31	G34619	126	128	0.61	0.20	43	2.3	15	34	0.1	51	AS7-5488a
M-07-31	G34620	128	130	0.61	0.19	22	2.4	30	36	5	66	AS7-5488a
M-07-31	G34621	130	132	0.73	0.17	38	2.3	0.1	32	0.1	49	AS7-5485a
M-07-31	G34622	132	134	0.80	0.26	23	2.8	0.1	28	10	45	AS7-5485a
M-07-31	G34623	134	136	0.78	0.23	37	2.8	0.1	30	0.1	31	AS7-5485a
M-07-31	G34624	136	138	0.68	0.29	32	3.6	0.1	44	0.1	42	AS7-5485a
M-07-31	G34625	138	140	0.78	0.17	43	2.1	0.1	28	0.1	55	AS7-5485a
M-07-31	G34627	140	142	0.40	0.18	48	2	0.1	20	0.1	45	AS7-5485a
M-07-31	G34628	142	144	0.56	0.17	31	1.8	0.1	24	0.1	45	AS7-5485a
M-07-31	G34629	144	146	0.74	0.19	81	2.1	0.1	26	15	44	AS7-5485a
M-07-31	G34630	146	148	0.75	0.19	77	2.1	0.1	26	0.1	52	AS7-5485a
M-07-31	G34631	148	150	0.81	0.22	94	3.1	20	164	0.1	261	AS7-5485a
M-07-31	G34632	150	152	0.67	0.19	37	2	15	34	5	77	AS7-5485a
M-07-31	G34633	152	154	0.92	0.21	88	2.5	20	28	0.1	64	AS7-5485a
M-07-31	G34634	154	156	0.92	0.26	47	2.9	5	22	0.1	61	AS7-5485a
M-07-31	G34635	156	158	1.36	0.41	136	4.2	0.1	28	0.1	56	AS7-5485a
M-07-31	G34636	158	160	0.64	0.17	51	1.7	0.1	40	5	182	AS7-5485a
M-07-31	G34637	160	162	0.69	0.18	83	1.8	0.1	30	5	132	AS7-5485a
M-07-31	G34638	162	164	0.83	0.25	59	2.2	0.1	30	5	135	AS7-5485a
M-07-31	G34639	164	166	0.84	0.21	109	1.9	0.1	36	20	135	AS7-5485a
M-07-31	G34642	166	168	0.75	0.19	60	1.8	0.1	32	10	115	AS7-5485a
M-07-31	G34643	168	170	0.61	0.28	66	3.3	10	32	0.1	99	AS7-5485a
M-07-31	G34644	170	172	0.77	0.16	51	3	40	44	5	206	AS7-5485a
M-07-31	G34645	172	174	0.73	0.23	72	2.9	25	180	0.1	279	AS7-5485a
M-07-31	G34646	174	176	0.58	0.15	34	1.6	0.1	56	5	232	AS7-5485a
M-07-31	G34647	176	178	0.44	0.13	53	1.2	0.1	60	5	174	AS7-5485a
M-07-31	G34648	178	180	0.55	0.15	63	1.4	0.1	38	5	174	AS7-5485a
M-07-31	G34649	180	182	0.58	0.16	85	1.7	0.1	36	0.1	103	AS7-5485a
M-07-31	G34650	182	184	0.61	0.20	79	1.8	0.1	40	15	142	AS7-5485a
M-07-31	G34651	184	186	0.77	0.21	196	2.5	15	34	5	142	AS7-5485a
M-07-31	G34652	186	188	0.79	0.21	97	2.4	0.1	36	0.1	260	AS7-5485a
M-07-31	G34653	188	190	0.48	0.12	60	1.2	0.1	38	10	271	AS7-5485a
M-07-31	G34654	190	192	0.57	0.16	80	2	0.1	32	10	236	AS7-5485a
M-07-31	G34655	192	194	0.76	0.43	1132	18	35	38	0.1	50	AS7-5485a
M-07-31	G34656	194	196	0.60	0.13	58	2.4	10	28	0.1	92	AS7-5499a
M-07-31	G34657	196	198	0.58	0.19	284	3.6	20	30	0.1	77	AS7-5499a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-31	G34658	198	200	0.65	0.21	126	3.7	15	62	0.1	159	AS7-5499a
M-07-31	G34659	200	202	0.76	0.23	108	2.2	10	18	0.1	201	AS7-5499a
M-07-31	G34661	202	204	0.62	0.15	77	1.8	15	48	0.1	115	AS7-5499a
M-07-31	G34662	204	206	0.58	0.13	57	1.6	15	22	0.1	102	AS7-5499a
M-07-31	G34663	206	208	0.52	0.14	88	1.8	10	20	0.1	73	AS7-5499a
M-07-31	G34664	208	210	0.47	0.15	71	2.1	15	22	0.1	109	AS7-5499a
M-07-31	G34665	210	212	0.68	0.17	79	1.9	10	18	0.1	86	AS7-5499a
M-07-31	G34666	212	214	0.40	0.13	71	1.6	10	20	0.1	128	AS7-5499a
M-07-31	G34667	214	216	0.25	0.07	25	1.1	10	16	0.1	82	AS7-5499a
M-07-31	G34668	216	218	0.64	0.08	32	2.2	70	18	0.1	79	AS7-5499a
M-07-31	G34669	218	220	0.87	0.16	60	5.2	35	20	0.1	74	AS7-5499a
M-07-31	G34671	220	222	0.64	0.19	56	4.6	15	24	0.1	73	AS7-5499a
M-07-31	G34672	222	224	0.41	0.13	101	4.3	20	28	0.1	80	AS7-5499a
M-07-31	G34673	224	226	0.36	0.13	86	6.5	25	32	0.1	59	AS7-5499a
M-07-31	G34674	226	228	0.27	0.11	34	3.7	15	20	0.1	97	AS7-5499a
M-07-31	G34675	228	230	0.70	0.18	59	10.9	25	370	0.1	295	AS7-5499a
M-07-31	G34676	230	232	0.45	0.09	24	5.8	25	124	0.1	197	AS7-5499a
M-07-31	G34677	232	233.16	0.80	0.10	27	4.7	30	104	0.1	192	AS7-5499a
M-07-32	G36644	7.62	9	0.26	0.10	12	1.3	105	200	10	64	AS7-5484a
M-07-32	G36645	9	11	0.13	0.18	16	1	0.1	34	5	63	AS7-5484a
M-07-32	G36646	11	13	0.32	0.23	58	1.6	20	24	5	50	AS7-5484a
M-07-32	G36647	13	15	0.57	0.36	9	2.5	15	48	0.1	79	AS7-5484a
M-07-32	G36648	15	17	0.29	0.11	11	2.5	10	22	30	60	AS7-5484a
M-07-32	G36649	17	19	0.25	0.08	9	0.4	10	54	0.1	78	AS7-5484a
M-07-32	G36650	19	21	0.24	0.17	13	0.7	0.1	38	0.1	64	AS7-5484a
M-07-32	G36651	21	23	0.15	0.16	9	0.5	0.1	110	0.1	46	AS7-5484a
M-07-32	G36652	23	25	0.19	0.13	8	0.4	0.1	34	0.1	53	AS7-5484a
M-07-32	G36654	25	27	0.49	0.44	13	1.7	10	56	0.1	43	AS7-5484a
M-07-32	G36655	27	28.7	0.16	0.13	43	0.7	25	50	0.1	49	AS7-5484a
M-07-32	G36656	28.7	30	0.49	0.13	10	1.8	65	42	10	44	AS7-5484a
M-07-32	G36657	30	32	0.29	0.11	46	0.8	20	40	10	63	AS7-5484a
M-07-32	G36658	32	34	0.08	0.06	17	0.4	30	36	15	74	AS7-5484a
M-07-32	G36659	34	36	0.11	0.09	25	0.5	25	40	10	62	AS7-5484a
M-07-32	G36660	36	38	0.07	0.08	11	0.7	30	62	15	74	AS7-5484a
M-07-32	G36661	38	40	0.18	0.24	20	2.3	35	96	15	64	AS7-5484a
M-07-32	G36662	40	42	0.73	0.15	22	0.9	25	52	10	74	AS7-5484a
M-07-32	G36663	42	44	0.06	0.08	9	0.5	25	62	5	61	AS7-5484a
M-07-32	G36664	44	46	0.05	0.05	11	0.5	35	80	10	57	AS7-5484a
M-07-32	G36666	46	48	0.13	0.13	11	0.8	5	64	0.1	82	AS7-5484a
M-07-32	G36667	48	50	0.06	0.09	8	0.8	30	78	10	89	AS7-5484a
M-07-32	G36668	50	52	0.15	0.10	15	1.1	45	118	20	112	AS7-5484a
M-07-32	G36669	52	54	0.10	0.10	13	0.6	25	66	30	106	AS7-5484a
M-07-32	G36670	54	56	0.05	0.08	14	0.9	30	118	15	83	AS7-5484a
M-07-32	G36671	56	58	0.10	0.12	8	1	40	68	15	77	AS7-5484a
M-07-32	G36672	58	60	0.07	0.08	11	0.3	15	66	15	96	AS7-5484a
M-07-32	G36673	60	62	0.06	0.07	8	0.3	30	36	10	40	AS7-5484a
M-07-32	G36674	62	64	0.11	0.13	20	0.8	30	40	0.1	56	AS7-5484a
M-07-32	G36675	64	66	0.37	0.22	11	1.5	0.1	44	0.1	64	AS7-5484a
M-07-32	G36676	66	68	0.06	0.05	5	0.6	0.1	30	0.1	37	AS7-5489a
M-07-32	G36677	68	70	0.20	0.12	27	1.5	10	52	10	44	AS7-5489a
M-07-32	G36678	70	72	0.08	0.08	5	1.2	15	40	0.1	42	AS7-5489a
M-07-32	G36679	72	74	0.31	0.15	14	1.1	0.1	44	15	71	AS7-5489a
M-07-32	G36680	74	76	0.18	0.11	7	1.1	15	42	0.1	84	AS7-5489a
M-07-32	G36681	76	78	0.09	0.09	0.1	0.9	0.1	54	0.1	67	AS7-5489a
M-07-32	G36682	78	80	0.43	0.16	8	1.3	25	38	5	75	AS7-5489a
M-07-32	G36683	80	82	0.12	0.14	7	1.3	0.1	30	10	61	AS7-5489a
M-07-32	G36684	82	84	0.30	0.09	8	2	55	50	30	58	AS7-5489a
M-07-32	G36685	84	86	0.30	0.08	8	2.6	55	46	40	78	AS7-5489a
M-07-32	G36687	86	88	0.26	0.17	12	1.7	5	36	15	67	AS7-5489a
M-07-32	G36688	88	90	0.27	0.11	8	2	35	50	10	114	AS7-5489a
M-07-32	G36689	90	92	0.33	0.19	19	1.2	0.1	42	25	64	AS7-5489a
M-07-32	G36690	92	94	0.10	0.08	4	0.5	0.1	38	0.1	47	AS7-5489a
M-07-32	G36691	94	96	0.18	0.10	11	0.9	35	56	10	93	AS7-5489a
M-07-32	G36693	96	97.6	1.07	0.14	14	5.8	40	74	25	104	AS7-5489a
M-07-32	G36694	97.6	99	0.18	0.10	21	1.3	40	36	0.1	29	AS7-5489a
M-07-32	G36695	99	101	0.19	0.03	24	0.7	50	32	15	42	AS7-5489a
M-07-32	G36696	101	103	0.09	0.05	40	0.5	35	32	0.1	35	AS7-5489a
M-07-32	G36697	103	105	0.19	0.02	15	0.7	30	30	0.1	23	AS7-5489a
M-07-32	G36698	105	107	1.12	0.08	27	3.1	55	50	15	31	AS7-5489a
M-07-32	G36699	107	109	0.22	0.06	46	0.5	40	24	0.1	22	AS7-5489a
M-07-32	G36701	109	111	0.26	0.03	15	0.4	40	40	5	29	AS7-5489a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-32	G36702	111	113	0.12	0.04	12	0.5	25	28	5	36	AS7-5489a
M-07-32	G36703	113	115	0.14	0.04	17	1.2	35	60	15	68	AS7-5489a
M-07-32	G36704	115	117	0.07	0.03	31	0.7	45	34	10	27	AS7-5489a
M-07-32	G36705	117	118.5	0.10	0.06	44	1.3	45	38	10	29	AS7-5489a
M-07-32	G36706	118.5	119.9	0.26	0.05	77	2.8	45	60	10	95	AS7-5489a
M-07-32	G36707	119.9	122	0.20	0.05	42	2.5	75	136	15	46	AS7-5489a
M-07-32	G36708	122	124	0.24	0.10	18	5.1	75	184	40	297	AS7-5489a
M-07-32	G36709	124	126	0.00	0.00	13	0.6	30	56	0.1	38	AS7-5489a
M-07-32	G36710	126	127.5	0.00	0.00	9	0.5	30	38	0.1	14	AS7-5489a
M-07-32	G36711	127.5	128.7	0.06	0.00	17	0.6	10	42	0.1	27	AS7-5490a
M-07-32	G36712	128.7	130	0.33	0.07	34	2.9	100	206	40	163	AS7-5490a
M-07-32	G36713	130	132	0.18	0.10	8	1.9	15	56	0.1	52	AS7-5490a
M-07-32	G36714	132	134	0.19	0.13	26	2	25	80	0.1	60	AS7-5490a
M-07-32	G36715	134	136	0.50	0.14	12	5	20	80	15	96	AS7-5490a
M-07-32	G36716	136	138	0.36	0.09	0.1	4.7	10	202	0.1	356	AS7-5490a
M-07-32	G36717	138	139.8	1.18	0.20	23	7.3	30	242	70	116	AS7-5490a
M-07-32	G36718	139.8	142	0.08	0.02	10	0.5	5	20	0.1	10	AS7-5490a
M-07-32	G36719	142	144	0.04	0.00	6	0.3	10	10	0.1	5	AS7-5490a
M-07-32	G36720	144	146	0.04	0.01	14	0.4	10	16	0.1	3	AS7-5490a
M-07-32	G36722	146	148	0.08	0.02	23	1.2	10	46	0.1	51	AS7-5490a
M-07-32	G36724	148	150	0.07	0.02	28	0.9	15	34	5	28	AS7-5490a
M-07-32	G36725	150	152	0.06	0.01	20	0.6	10	26	0.1	20	AS7-5490a
M-07-32	G36726	152	154	0.19	0.11	12	2.3	20	60	15	54	AS7-5490a
M-07-32	G36727	154	156	0.14	0.11	17	2.5	15	56	0.1	51	AS7-5490a
M-07-32	G36728	156	158	0.58	0.21	27	28	20	1508	65	122	AS7-5490a
M-07-32	G36729	158	160	0.46	0.14	17	4.8	25	104	20	146	AS7-5490a
M-07-32	G36730	160	162	0.61	0.37	1	4.2	20	82	0.1	132	AS7-5490a
M-07-32	G36731	162	164	0.44	0.16	24	2.1	15	166	30	227	AS7-5490a
M-07-32	G36732	164	166	0.08	0.10	22	1.3	15	180	35	185	AS7-5490a
M-07-32	G36733	166	168	0.13	0.07	10	1.7	10	280	20	163	AS7-5490a
M-07-32	G36734	168	170	0.07	0.15	20	1.6	15	190	35	149	AS7-5490a
M-07-32	G36736	170	172	0.08	0.14	56	1.3	20	102	0.1	98	AS7-5490a
M-07-32	G36737	172	174	0.15	0.15	15	2.8	35	240	10	123	AS7-5490a
M-07-32	G36738	174	176	0.18	0.15	17	3.1	20	322	20	148	AS7-5490a
M-07-32	G36739	176	178	0.07	0.05	11	3.1	30	844	20	129	AS7-5490a
M-07-32	G36740	178	180	0.26	0.12	49	3.3	60	522	30	90	AS7-5490a
M-07-32	G36741	180	182	0.24	0.15	12	2.3	45	100	10	48	AS7-5490a
M-07-32	G36742	182	184	0.23	0.14	13	1.8	35	140	0.1	68	AS7-5490a
M-07-32	G36743	184	186	0.09	0.14	20	1.1	25	92	30	123	AS7-5490a
M-07-32	G36744	186	188	0.03	0.06	36	2.4	20	348	10	87	AS7-5490a
M-07-32	G36745	188	190	0.06	0.34	95	2.9	20	258	50	91	AS7-5490a
M-07-32	G36746	190	192	0.34	0.16	45	2.5	40	186	0.1	104	AS7-5491a
M-07-32	G36747	192	194	0.11	0.17	87	3.4	40	322	10	159	AS7-5491a
M-07-32	G36748	194	196	0.32	0.19	18	2.9	50	200	15	115	AS7-5491a
M-07-32	G36749	196	198	0.46	0.14	6	2.8	40	74	0.1	50	AS7-5491a
M-07-32	G36750	198	200	0.14	0.08	34	1	50	78	5	81	AS7-5491a
M-07-32	G36751	200	202	0.11	0.16	12	2.2	60	216	0.1	90	AS7-5491a
M-07-32	G36752	202	204	0.39	0.10	60	1.5	50	146	20	98	AS7-5491a
M-07-32	G36753	204	206	0.61	0.07	33	2.7	60	54	10	76	AS7-5491a
M-07-32	G36754	206	208	0.19	0.07	36	3.2	50	94	0.1	43	AS7-5491a
M-07-32	G36756	208	210	0.15	0.10	17	1.6	60	58	5	69	AS7-5491a
M-07-32	G36757	210	212	0.06	0.19	63	2	55	56	10	61	AS7-5491a
M-07-32	G36758	212	214	0.08	0.07	62	1.3	55	60	10	52	AS7-5491a
M-07-32	G36759	214	216	0.08	0.07	57	1.7	40	72	0.1	148	AS7-5491a
M-07-32	G36760	216	217.4	0.13	0.03	9	0.7	45	38	15	40	AS7-5491a
M-07-32	G36761	217.4	219	0.05	0.01	7	0.7	50	34	15	40	AS7-5491a
M-07-32	G36762	219	221	0.06	0.01	16	0.5	30	56	5	88	AS7-5491a
M-07-32	G36763	221	223	0.16	0.01	10	0.7	30	62	0.1	55	AS7-5491a
M-07-32	G36764	223	223.9	0.12	0.02	20	1	30	62	0.1	60	AS7-5491a
M-07-32	G36765	223.9	225	0.20	0.06	42	2.9	40	214	0.1	53	AS7-5491a
M-07-32	G36766	225	227	1.05	0.12	24	2.1	45	44	0.1	38	AS7-5491a
M-07-32	G36767	227	229	0.45	0.07	42	1.3	35	52	10	41	AS7-5491a
M-07-32	G36768	229	231	0.13	0.07	15	1.7	60	54	0.1	33	AS7-5491a
M-07-32	G36770	231	233	0.20	0.08	11	2.3	75	68	0.1	69	AS7-5491a
M-07-32	G36771	233	234.7	0.27	0.10	15	2.3	45	68	0.1	25	AS7-5491a
M-07-32	G36772	234.7	236	0.37	0.02	10	1.5	50	54	0.1	65	AS7-5491a
M-07-32	G36773	236	238	0.12	0.01	4	0.5	45	34	10	66	AS7-5491a
M-07-32	G36774	238	240	0.09	0.01	5	0.8	90	32	15	65	AS7-5491a
M-07-32	G36775	240	242	0.12	0.01	3	1.3	70	32	0.1	73	AS7-5491a
M-07-32	G36776	242	244	0.13	0.01	3	1.3	50	32	0.1	73	AS7-5491a
M-07-32	G36777	244	246	0.14	0.02	5	1.4	65	30	0.1	49	AS7-5491a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-32	G36778	246	248	0.38	0.01	5	1.1	50	50	0.1	31	AS7-5491a
M-07-32	G36779	248	250	0.15	0.00	5	0.6	40	52	0.1	26	AS7-5491a
M-07-32	G36780	250	252	0.05	0.02	4	1.5	45	70	0.1	138	AS7-5491a
M-07-32	G36781	252	254	0.18	0.02	30	2.6	35	96	0.1	46	AS7-5492a
M-07-32	G36782	254	255.15	0.21	0.04	8	1.8	25	36	10	109	AS7-5492a
M-07-32	G36783	255.15	257	0.09	0.01	9	0.6	20	72	10	67	AS7-5492a
M-07-32	G36784	257	259	0.09	0.01	7	0.9	30	52	10	64	AS7-5492a
M-07-32	G36785	259	261	0.12	0.01	7	0.4	15	40	15	69	AS7-5492a
M-07-32	G36786	261	263	0.13	0.01	9	0.5	25	48	25	80	AS7-5492a
M-07-32	G36787	263	265	0.12	0.01	6	0.7	25	52	0.1	98	AS7-5492a
M-07-32	G36788	265	267	0.16	0.01	5	0.8	15	52	0.1	69	AS7-5492a
M-07-32	G36789	267	269	0.10	0.01	7	0.3	20	50	0.1	59	AS7-5492a
M-07-32	G36790	269	271	0.14	0.01	4	0.5	15	44	10	66	AS7-5492a
M-07-32	G36791	271	273	0.08	0.01	5	0.2	40	40	10	60	AS7-5492a
M-07-32	G36792	273	275	0.09	0.01	6	0.7	55	40	15	51	AS7-5492a
M-07-32	G36794	275	277	0.09	0.01	8	1	45	90	0.1	39	AS7-5492a
M-07-32	G36795	277	279	0.10	0.02	4	1.2	70	36	15	55	AS7-5492a
M-07-32	G36797	279	281	0.15	0.01	9	0.4	70	48	30	37	AS7-5492a
M-07-32	G36798	281	283	0.18	0.02	5	0.5	75	38	10	28	AS7-5492a
M-07-32	G36799	283	285	0.12	0.01	8	0.3	45	54	10	22	AS7-5492a
M-07-32	G36800	285	287	0.10	0.01	8	0.3	60	38	0.1	17	AS7-5492a
M-07-32	G36801	287	289	0.10	0.01	3	0.5	65	36	5	32	AS7-5492a
M-07-32	G36802	289	291	0.08	0.02	7	0.6	95	36	20	40	AS7-5492a
M-07-32	G36803	291	293	0.08	0.01	5	0.4	50	42	5	35	AS7-5492a
M-07-32	G36804	293	295	0.07	0.00	7	0.2	50	38	10	27	AS7-5492a
M-07-32	G36805	295	297	0.07	0.00	5	0.01	50	42	5	34	AS7-5492a
M-07-32	G36806	297	299	0.06	0.00	6	0.01	45	44	0.1	22	AS7-5492a
M-07-32	G36807	299	301	0.09	0.01	8	0.8	55	78	15	60	AS7-5492a
M-07-32	G36808	301	303	0.11	0.01	6	0.7	75	58	10	51	AS7-5492a
M-07-32	G36809	303	305	0.09	0.00	5	0.6	50	52	0.1	20	AS7-5492a
M-07-32	G36811	305	307	0.10	0.01	10	0.4	50	50	15	35	AS7-5492a
M-07-32	G36812	307	309	0.09	0.01	9	0.4	50	56	10	34	AS7-5492a
M-07-32	G36813	309	311	0.07	0.01	7	0.5	55	126	10	37	AS7-5492a
M-07-32	G36814	311	313	0.09	0.00	9	0.2	30	62	0.1	43	AS7-5492a
M-07-32	G36815	313	315	0.10	0.01	18	0.6	50	46	0.1	26	AS7-5492a
M-07-32	G36816	315	317	0.11	0.01	3	1.1	45	52	20	62	AS7-5505a
M-07-32	G36817	317	319	0.04	0.01	0.1	0.8	30	66	10	42	AS7-5505a
M-07-32	G36818	319	321	0.09	0.01	1	0.8	30	30	15	40	AS7-5505a
M-07-32	G36819	321	323	0.07	0.01	0.1	1.1	40	26	20	44	AS7-5505a
M-07-32	G36820	323	325	0.06	0.00	2	0.2	15	20	0.1	23	AS7-5505a
M-07-32	G36821	325	327	0.07	0.00	0.1	0.01	15	28	0.1	22	AS7-5505a
M-07-32	G36822	327	329	0.08	0.01	2	0.3	15	24	0.1	29	AS7-5505a
M-07-32	G36823	329	331.25	0.06	0.00	0.1	0.3	20	30	0.1	29	AS7-5505a
M-07-32	G36824	331.25	333	0.07	0.01	1	0.2	10	12	0.1	33	AS7-5505a
M-07-32	G36825	333	335	0.09	0.01	0.1	0.2	15	12	0.1	39	AS7-5505a
M-07-32	G36826	335	337	0.10	0.01	0.1	0.4	10	14	0.1	35	AS7-5505a
M-07-32	G36827	337	339	0.09	0.01	0.1	0.4	15	14	0.1	37	AS7-5505a
M-07-32	G36828	339	340.16	0.10	0.01	1	0.3	15	14	0.1	51	AS7-5505a
M-07-32	G36829	340.16	342	0.12	0.00	0.1	0.4	20	28	0.1	33	AS7-5505a
M-07-32	G36830	342	344	0.11	0.01	2	0.2	15	24	0.1	36	AS7-5505a
M-07-32	G36831	344	346	0.10	0.01	1	0.3	15	20	0.1	36	AS7-5505a
M-07-32	G36833	346	348	0.16	0.01	2	0.5	15	28	0.1	36	AS7-5505a
M-07-32	G36834	348	350	0.10	0.01	1	0.4	15	76	0.1	180	AS7-5505a
M-07-32	G36835	350	352	0.11	0.00	1	0.4	20	40	0.1	53	AS7-5505a
M-07-32	G36837	352	354	0.12	0.00	4	0.4	30	20	0.1	32	AS7-5505a
M-07-32	G36838	354	356	0.28	0.00	3	0.4	30	24	0.1	24	AS7-5505a
M-07-32	G36839	356	358	0.08	0.00	2	0.5	25	54	0.1	32	AS7-5505a
M-07-32	G36840	358	360	0.08	0.00	9	0.4	25	46	0.1	22	AS7-5505a
M-07-32	G36841	360	362	0.16	0.00	2	0.6	45	54	5	17	AS7-5505a
M-07-32	G36842	362	363.3	0.07	0.00	1	0.4	30	26	5	38	AS7-5505a
M-07-32	G36843	363.3	364.54	0.14	0.02	0.1	0.7	35	30	0.1	33	AS7-5505a
M-07-33	G34678	12.2	14	0.06	0.20	23	1.2	5	8	0.1	21	AS7-5499a
M-07-33	G34679	14	16	0.08	0.25	30	1.6	10	10	0.1	29	AS7-5499a
M-07-33	G34680	16	18	0.08	0.13	9	0.8	10	6	0.1	18	AS7-5499a
M-07-33	G34681	18	20	0.15	0.07	6	0.4	10	8	0.1	16	AS7-5499a
M-07-33	G34682	20	22	0.13	0.10	29	0.7	10	8	0.1	23	AS7-5499a
M-07-33	G34683	22	24	0.16	0.17	49	1	5	6	0.1	21	AS7-5499a
M-07-33	G34684	24	26	0.08	0.27	17	1.9	10	10	0.1	27	AS7-5499a
M-07-33	G34685	26	28	0.04	0.17	17	1.1	10	8	0.1	25	AS7-5499a
M-07-33	G34686	28	30	0.03	0.05	4	0.4	0.1	6	0.1	17	AS7-5499a
M-07-33	G34687	30	32	0.05	0.10	5	0.8	5	6	0.1	20	AS7-5499a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-33	G34688	32	34	0.11	0.29	5	1.8	10	12	0.1	44	AS7-5499a
M-07-33	G34689	34	36	0.32	0.19	4	1.5	20	12	0.1	29	AS7-5499a
M-07-33	G34690	36	38	0.26	0.36	7	2.1	5	12	0.1	50	AS7-5499a
M-07-33	G34691	38	40	0.33	0.27	10	2.1	0.1	24	0.1	42	AS7-5500a
M-07-33	G34692	40	42	0.23	0.49	9	2.6	0.1	12	5	53	AS7-5500a
M-07-33	G34693	42	44	0.26	0.26	6	1.6	10	14	0.1	34	AS7-5500a
M-07-33	G34694	44	46	0.12	0.27	17	1.7	0.1	12	0.1	43	AS7-5500a
M-07-33	G34695	46	48	0.14	0.14	4	1.1	0.1	10	0.1	26	AS7-5500a
M-07-33	G34696	48	50	0.07	0.12	5	0.9	0.1	12	0.1	37	AS7-5500a
M-07-33	G34697	50	52	0.05	0.18	8	1.3	0.1	14	5	53	AS7-5500a
M-07-33	G34698	52	54	0.09	0.13	6	1.1	0.1	14	10	46	AS7-5500a
M-07-33	G34699	54	56	0.11	0.09	4	0.8	0.1	10	15	69	AS7-5500a
M-07-33	G34700	56	58	0.04	0.01	4	0.5	0.1	10	0.1	45	AS7-5500a
M-07-33	G34701	58	60	0.46	0.09	6	2.6	25	16	20	52	AS7-5500a
M-07-33	G34702	60	62	0.20	0.14	9	2	25	12	35	63	AS7-5500a
M-07-33	G34703	62	64	0.11	0.05	106	1	15	14	15	35	AS7-5500a
M-07-33	G34704	64	66	0.54	0.10	26	2.2	55	12	40	40	AS7-5500a
M-07-33	G34705	66	68	0.29	0.24	12	2.2	20	10	0.1	24	AS7-5500a
M-07-33	G34706	68	70	0.08	0.15	6	1.3	0.1	14	0.1	16	AS7-5500a
M-07-33	G34707	70	72	0.06	0.13	5	1	0.1	10	0.1	17	AS7-5500a
M-07-33	G34708	72	74	0.04	0.09	5	0.7	10	6	5	17	AS7-5500a
M-07-33	G34709	74	76	0.31	0.09	4	2.2	70	20	45	24	AS7-5500a
M-07-33	G34711	76	78	0.17	0.09	3	1.5	30	18	30	25	AS7-5500a
M-07-33	G34712	78	80	0.19	0.07	3	2.2	35	12	30	70	AS7-5500a
M-07-33	G34713	80	82	0.22	0.16	5	2.3	30	38	10	71	AS7-5500a
M-07-33	G34715	82	84	0.15	0.01	20	2.2	25	126	10	64	AS7-5500a
M-07-33	G34716	84	86	0.21	0.02	12	2	100	122	65	86	AS7-5500a
M-07-33	G34717	86	88	0.13	0.01	38	1.8	30	82	30	30	AS7-5500a
M-07-33	G34719	88	90	0.28	0.02	29	1	85	40	30	34	AS7-5500a
M-07-33	G34720	90	92	0.18	0.01	14	0.8	60	26	10	15	AS7-5500a
M-07-33	G34721	92	94	0.17	0.01	36	0.7	30	26	10	24	AS7-5500a
M-07-33	G34722	94	96	0.21	0.02	14	0.9	10	32	10	33	AS7-5500a
M-07-33	G34723	96	98	0.07	0.01	24	0.4	0.1	18	0.1	24	AS7-5500a
M-07-33	G34724	98	100	0.33	0.02	75	1.1	15	36	10	32	AS7-5500a
M-07-33	G34725	100	102	0.46	0.01	24	1.5	10	146	10	453	AS7-5500a
M-07-33	G34726	102	104	0.31	0.02	20	1.5	25	86	25	64	AS7-5501a
M-07-33	G34727	104	106	0.12	0.01	19	0.7	20	22	15	13	AS7-5501a
M-07-33	G34728	106	108	0.28	0.02	181	3.7	25	230	25	82	AS7-5501a
M-07-33	G34729	108	110	0.21	0.01	33	2.5	20	166	10	22	AS7-5501a
M-07-33	G34730	110	112	0.24	0.01	11	1.2	20	18	0.1	25	AS7-5501a
M-07-33	G34731	112	114	0.20	0.02	17	1.6	20	26	15	57	AS7-5501a
M-07-33	G34732	114	116	0.10	0.03	18	1.6	35	24	40	30	AS7-5501a
M-07-33	G34733	116	118	0.07	0.03	22	0.7	25	18	15	13	AS7-5501a
M-07-33	G34734	118	120	0.05	0.05	69	3.4	70	44	65	48	AS7-5501a
M-07-33	G34735	120	122	0.06	0.04	32	2.4	30	34	30	39	AS7-5501a
M-07-33	G34736	122	124	0.04	0.03	17	1	25	26	20	31	AS7-5501a
M-07-33	G34737	124	126	0.05	0.05	102	1.7	30	22	35	49	AS7-5501a
M-07-33	G34738	126	128	0.04	0.07	157	2.7	45	16	95	83	AS7-5501a
M-07-33	G34739	128	130	0.20	0.01	9	1.9	25	90	5	39	AS7-5501a
M-07-33	G34740	130	132	0.22	0.01	7	1.8	35	38	0.1	34	AS7-5501a
M-07-33	G34741	132	134	0.31	0.00	6	1.7	60	42	0.1	16	AS7-5501a
M-07-33	G34742	134	136	0.42	0.03	5	2.2	30	36	0.1	39	AS7-5501a
M-07-33	G34743	136	138	0.56	0.01	7	2.2	50	22	5	27	AS7-5501a
M-07-33	G34744	138	140	0.27	0.02	5	1.3	50	12	5	28	AS7-5501a
M-07-33	G34745	140	142	0.11	0.01	4	1	10	12	0.1	24	AS7-5501a
M-07-33	G34746	142	144	0.42	0.00	8	2.8	20	32	0.1	40	AS7-5501a
M-07-33	G34747	144	146	0.49	0.01	34	4.3	25	148	0.1	57	AS7-5501a
M-07-33	G34748	146	148	0.30	0.00	11	1.6	25	50	0.1	46	AS7-5501a
M-07-33	G34751	148	150	0.29	0.00	7	1.4	25	40	0.1	38	AS7-5501a
M-07-33	G34752	150	151.8	0.24	0.02	22	1.7	35	94	5	66	AS7-5501a
M-07-33	G34753	151.8	154.6	0.12	0.05	3	0.6	15	8	10	48	AS7-5501a
M-07-33	G34754	154.6	156	0.08	0.02	41	1.9	25	182	0.1	33	AS7-5501a
M-07-33	G34755	156	158	0.10	0.01	47	1.1	40	66	5	55	AS7-5501a
M-07-33	G34756	158	160	0.09	0.01	12	0.6	50	50	0.1	28	AS7-5501a
M-07-33	G34757	160	162	0.07	0.02	2	0.8	30	18	15	43	AS7-5501a
M-07-33	G34758	162	164	0.17	0.02	5	0.9	50	68	10	46	AS7-5501a
M-07-33	G34759	164	166	0.14	0.01	12	1.1	45	262	0.1	134	AS7-5501a
M-07-33	G34760	166	168	0.68	0.10	18	1.8	25	56	15	121	AS7-5501a
M-07-33	G34761	168	170	0.36	0.07	18	0.9	10	14	10	80	AS7-5502a
M-07-33	G34762	170	172	0.52	0.11	17	1.1	10	16	5	60	AS7-5502a
M-07-33	G34763	172	174	0.34	0.05	12	0.5	0.1	20	0.1	72	AS7-5502a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-33	G34764	174	175.5	0.42	0.06	12	1.6	70	74	15	102	AS7-5502a
M-07-33	G34765	175.5	178	0.32	0.12	51	1.7	70	224	10	35	AS7-5502a
M-07-33	G34766	178	180	0.26	0.07	234	1	60	106	10	32	AS7-5502a
M-07-33	G34767	180	182	0.10	0.05	55	0.3	35	22	10	29	AS7-5502a
M-07-33	G34768	182	184	0.31	0.21	47	1	40	24	5	23	AS7-5502a
M-07-33	G34769	184	186	0.07	0.01	7	0.4	30	38	10	57	AS7-5502a
M-07-33	G34770	186	188	0.13	0.08	35	0.4	0.1	42	15	53	AS7-5502a
M-07-33	G34771	188	190	0.00	0.01	5	0.2	15	26	0.1	25	AS7-5502a
M-07-33	G34772	190	192	0.06	0.04	12	0.01	20	30	5	31	AS7-5502a
M-07-33	G34774	192	193.6	0.05	0.03	9	0.01	15	22	0.1	23	AS7-5502a
M-07-33	G34775	193.6	196	0.19	0.07	36	0.3	20	36	0.1	31	AS7-5502a
M-07-33	G34776	196	198	0.37	0.04	6	0.9	90	68	5	61	AS7-5502a
M-07-33	G34778	198	200	0.08	0.04	19	0.4	20	26	0.1	23	AS7-5502a
M-07-33	G34779	200	202	0.09	0.05	17	0.2	10	30	10	20	AS7-5502a
M-07-33	G34780	202	204	0.05	0.03	11	0.01	10	26	10	22	AS7-5502a
M-07-33	G34781	204	206	0.00	0.02	7	0.3	25	26	10	20	AS7-5502a
M-07-33	G34782	206	208	0.25	0.12	22	0.4	15	36	0.1	26	AS7-5502a
M-07-33	G34783	208	210	0.15	0.10	17	0.5	35	40	15	51	AS7-5502a
M-07-33	G34784	210	212	0.13	0.07	17	0.4	40	34	20	41	AS7-5502a
M-07-33	G34785	212	214	0.06	0.04	14	0.3	35	30	15	27	AS7-5502a
M-07-33	G34786	214	216	0.28	0.05	10	0.6	30	26	10	16	AS7-5502a
M-07-33	G34787	216	218	0.40	0.08	10	0.4	0.1	26	10	29	AS7-5502a
M-07-33	G34788	218	220	0.22	0.04	12	0.3	35	34	10	24	AS7-5502a
M-07-33	G34789	220	222	0.16	0.04	10	0.01	10	32	10	43	AS7-5502a
M-07-33	G34790	222	224	0.07	0.04	13	0.2	15	32	0.1	28	AS7-5502a
M-07-33	G34791	224	226	0.16	0.09	14	0.3	15	26	0.1	27	AS7-5502a
M-07-33	G34792	226	228	0.09	0.04	16	0.3	15	42	15	59	AS7-5502a
M-07-33	G34793	228	230	0.08	0.04	21	0.2	10	26	0.1	19	AS7-5502a
M-07-33	G34794	230	232	0.13	0.06	25	0.2	25	24	0.1	15	AS7-5502a
M-07-33	G34796	232	234	0.14	0.04	21	0.3	10	20	0.1	13	AS7-5503a
M-07-33	G34797	234	236	0.08	0.04	9	0.2	0.1	22	0.1	14	AS7-5503a
M-07-33	G34798	236	238	0.17	0.04	5	0.2	0.1	24	0.1	15	AS7-5503a
M-07-33	G34799	238	240	0.05	0.03	5	0.01	0.1	26	0.1	30	AS7-5503a
M-07-33	G34800	240	242	0.41	0.11	15	0.6	30	82	10	27	AS7-5503a
M-07-33	G34801	242	244	0.35	0.04	8	0.2	50	26	0.1	17	AS7-5503a
M-07-33	G34802	244	246	14.70	0.11	14	1	105	34	15	29	AS7-5503a
M-07-33	G34803	246	248	0.78	0.06	25	0.2	75	32	0.1	23	AS7-5503a
M-07-33	G34804	248	250	1.69	0.06	26	0.4	135	40	20	29	AS7-5503a
M-07-33	G34805	250	252	0.10	0.04	14	0.2	20	30	0.1	24	AS7-5503a
M-07-33	G34806	252	254	0.57	0.10	31	0.5	20	38	15	30	AS7-5503a
M-07-33	G34807	254	256	0.27	0.13	11	0.4	15	48	0.1	46	AS7-5503a
M-07-33	G34808	256	258	0.25	0.04	12	0.5	10	78	0.1	164	AS7-5503a
M-07-33	G34809	258	260	0.22	0.04	14	0.5	30	58	20	278	AS7-5503a
M-07-33	G34810	260	262	0.42	0.05	31	0.8	35	54	35	132	AS7-5503a
M-07-33	G34811	262	264	0.10	0.03	32	0.3	20	36	0.1	36	AS7-5503a
M-07-33	G34812	264	266	0.34	0.10	23	0.7	20	40	10	44	AS7-5503a
M-07-33	G34813	266	268	0.30	0.05	25	0.6	35	72	20	164	AS7-5503a
M-07-33	G34814	268	270	0.54	0.08	38	0.6	20	48	20	74	AS7-5503a
M-07-33	G34815	270	272	3.60	0.06	79	0.8	20	54	15	57	AS7-5503a
M-07-33	G34816	272	274	0.34	0.05	118	0.6	25	46	0.1	72	AS7-5503a
M-07-33	G34817	274	276	0.68	0.03	38	0.7	40	64	10	111	AS7-5503a
M-07-33	G34818	276	278	0.60	0.03	13	0.9	60	70	15	105	AS7-5503a
M-07-33	G34819	278	280	0.20	0.05	9	0.7	40	50	0.1	75	AS7-5503a
M-07-33	G34820	280	282	1.25	0.17	17	1.2	25	66	20	97	AS7-5503a
M-07-33	G34821	282	284	1.02	0.10	61	1.1	30	58	0.1	76	AS7-5503a
M-07-33	G34822	284	286	1.29	0.17	30	2.5	50	100	20	408	AS7-5503a
M-07-33	G34823	286	288	0.68	0.06	56	1.2	40	114	15	281	AS7-5503a
M-07-33	G34824	288	290	0.40	0.02	14	0.3	45	84	35	144	AS7-5503a
M-07-33	G34826	290	292	0.26	0.01	14	0.4	50	90	20	122	AS7-5503a
M-07-33	G34827	292	294	0.30	0.03	35	1.3	45	116	30	157	AS7-5503a
M-07-33	G34828	294	296	0.55	0.04	41	2.2	50	112	30	198	AS7-5503a
M-07-33	G34830	296	298	0.38	0.03	15	0.4	50	104	20	64	AS7-5503a
M-07-33	G34831	298	300	0.23	0.03	10	0.3	20	26	0.1	30	AS7-5504a
M-07-33	G34832	300	302	0.08	0.04	11	0.4	20	20	0.1	39	AS7-5504a
M-07-33	G34833	302	304	0.09	0.04	4	0.3	30	16	0.1	42	AS7-5504a
M-07-33	G34834	304	306	0.21	0.05	14	0.4	35	34	0.1	45	AS7-5504a
M-07-33	G34835	306	308	0.42	0.04	15	0.8	40	70	0.1	86	AS7-5504a
M-07-33	G34836	308	310	0.22	0.05	6	0.5	25	108	0.1	100	AS7-5504a
M-07-33	G34837	310	312	0.21	0.05	10	0.9	30	190	0.1	130	AS7-5504a
M-07-33	G34838	312	314	0.30	0.03	15	1.6	35	178	0.1	167	AS7-5504a
M-07-33	G34839	314	316	5.77	0.06	19	3.8	35	74	0.1	151	AS7-5504a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-33	G34840	316	318	0.61	0.13	19	1	40	56	0.1	138	AS7-5504a
M-07-33	G34841	318	320	0.37	0.04	28	0.8	40	56	0.1	141	AS7-5504a
M-07-33	G34842	320	322	0.24	0.03	18	0.4	40	44	0.1	153	AS7-5504a
M-07-33	G34843	322	324	0.75	0.03	31	0.5	35	56	0.1	168	AS7-5504a
M-07-33	G34844	324	326	0.76	0.06	25	1.4	35	126	0.1	181	AS7-5504a
M-07-33	G34846	326	328	0.39	0.02	19	0.9	40	88	0.1	97	AS7-5504a
M-07-33	G34847	328	330	0.26	0.02	50	0.4	35	30	0.1	165	AS7-5504a
M-07-33	G34848	330	332	0.35	0.04	28	0.7	50	34	0.1	164	AS7-5504a
M-07-33	G34849	332	334	0.28	0.02	15	0.7	45	42	0.1	167	AS7-5504a
M-07-33	G34850	334	336	0.28	0.10	12	2.8	30	84	0.1	176	AS7-5504a
M-07-33	G34851	336	338	0.12	0.03	17	0.9	55	42	0.1	64	AS7-5504a
M-07-33	G34852	338	340	0.13	0.02	15	1.2	40	72	10	107	AS7-5504a
M-07-33	G34853	340	342	0.19	0.06	29	1.3	40	26	5	55	AS7-5504a
M-07-33	G34854	342	344	0.19	0.04	16	1.4	25	142	0.1	82	AS7-5504a
M-07-33	G34855	344	346	0.18	0.04	2	0.8	25	36	0.1	87	AS7-5504a
M-07-33	G34856	346	348	0.14	0.02	3	0.5	25	22	0.1	34	AS7-5504a
M-07-33	G34857	348	350	0.16	0.04	7	0.4	40	18	0.1	28	AS7-5504a
M-07-33	G34858	350	352	0.12	0.03	6	0.4	25	20	0.1	22	AS7-5504a
M-07-33	G34859	352	354	0.16	0.01	5	0.4	35	42	0.1	34	AS7-5504a
M-07-33	G34860	354	356	0.10	0.02	4	0.5	30	42	0.1	44	AS7-5504a
M-07-33	G34861	356	358	0.31	0.02	3	0.5	35	32	0.1	52	AS7-5504a
M-07-33	G34862	358	360	0.26	0.02	4	0.4	115	36	0.1	51	AS7-5504a
M-07-33	G34865	360	362	0.26	0.06	13	0.6	35	64	0.1	46	AS7-5504a
M-07-33	G34866	362	364	0.19	0.01	4	0.7	20	28	0.1	64	AS7-5511a
M-07-33	G34867	364	366	0.25	0.04	28	1.4	35	36	0.1	16	AS7-5511a
M-07-33	G34868	366	368	0.33	0.04	34	1.3	45	80	0.1	26	AS7-5511a
M-07-33	G34869	368	370	0.22	0.03	12	1.1	45	28	0.1	14	AS7-5511a
M-07-33	G34870	370	372	0.58	0.05	10	1.6	35	24	10	34	AS7-5511a
M-07-33	G34871	372	374	1.14	0.04	4	1.4	45	26	0.1	16	AS7-5511a
M-07-33	G34872	374	376	0.83	0.02	4	1.6	90	30	15	16	AS7-5511a
M-07-33	G34873	376	378	0.58	0.02	9	1.3	55	20	25	15	AS7-5511a
M-07-33	G34874	378	380	0.42	0.02	3	0.9	35	18	10	11	AS7-5511a
M-07-33	G34875	380	382	0.23	0.02	4	1	40	24	10	24	AS7-5511a
M-07-33	G34876	382	384	0.25	0.02	4	1	65	22	0.1	21	AS7-5511a
M-07-33	G34877	384	386	0.17	0.02	3	1	35	28	10	38	AS7-5511a
M-07-33	G34878	386	388	0.26	0.02	8	1.6	45	30	0.1	21	AS7-5511a
M-07-33	G34879	388	390	0.60	0.04	6	1.5	50	16	0.1	11	AS7-5511a
M-07-33	G34880	390	392	0.31	0.01	26	1.5	55	34	5	44	AS7-5511a
M-07-33	G34881	392	394	0.31	0.01	4	1.8	80	56	0.1	26	AS7-5511a
M-07-33	G34882	394	396	0.28	0.01	3	0.9	45	18	0.1	30	AS7-5511a
M-07-33	G34883	396	398	0.46	0.03	5	1.5	60	28	15	31	AS7-5511a
M-07-33	G34884	398	400	0.35	0.01	6	1.2	60	22	5	28	AS7-5511a
M-07-33	G34885	400	402	0.45	0.03	8	1.5	95	20	10	35	AS7-5511a
M-07-33	G34886	402	404	0.19	0.01	3	1	60	36	0.1	89	AS7-5511a
M-07-33	G34887	404	406	0.26	0.02	3	1.2	40	24	10	24	AS7-5511a
M-07-33	G34888	406	408	0.21	0.03	5	1.7	60	170	15	340	AS7-5511a
M-07-33	G34889	408	410	0.20	0.01	5	1.4	90	24	15	27	AS7-5511a
M-07-33	G34891	410	412	0.38	0.02	6	1.5	50	20	5	23	AS7-5511a
M-07-33	G34892	412	414	0.17	0.01	2	0.8	25	22	0.1	15	AS7-5511a
M-07-33	G34893	414	416	0.34	0.02	5	1.4	60	48	0.1	41	AS7-5511a
M-07-33	G34894	416	418	1.29	0.02	8	3.2	90	88	40	75	AS7-5511a
M-07-33	G34895	418	420	0.54	0.02	10	1.9	50	34	20	52	AS7-5511a
M-07-33	G34896	420	422	0.09	0.02	6	1.7	55	28	10	16	AS7-5511a
M-07-33	G34898	422	424	0.11	0.02	14	1.9	65	38	15	19	AS7-5511a
M-07-33	G34899	424	426	0.15	0.03	13	3	70	38	10	22	AS7-5511a
M-07-33	G34900	426	428	0.16	0.03	24	1.8	45	52	5	26	AS7-5511a
M-07-33	G34901	428	430	0.22	0.05	16	1.6	25	44	5	24	AS7-5512a
M-07-33	G34902	430	432	0.20	0.03	24	1.3	35	30	5	17	AS7-5512a
M-07-33	G34903	432	434	0.13	0.02	5	0.9	30	22	5	22	AS7-5512a
M-07-33	G34904	434	436	0.94	0.04	17	1.3	35	26	10	19	AS7-5512a
M-07-33	G34905	436	438	1.51	0.05	18	1.3	40	34	0.1	19	AS7-5512a
M-07-33	G34906	438	440	0.82	0.03	25	1.2	30	28	10	28	AS7-5512a
M-07-33	G34907	440	442	0.54	0.02	16	1.8	45	38	5	28	AS7-5512a
M-07-33	G34908	442	444	0.74	0.02	5	2.4	50	54	10	27	AS7-5512a
M-07-33	G34909	444	446	0.76	0.02	28	3.9	120	198	5	133	AS7-5512a
M-07-33	G34910	446	448	0.16	0.01	7	1.3	40	50	15	85	AS7-5512a
M-07-33	G34911	448	450	0.33	0.02	6	1.4	80	40	10	37	AS7-5512a
M-07-33	G34912	450	452	0.11	0.02	31	1.1	55	22	5	18	AS7-5512a
M-07-33	G34913	452	454	0.21	0.03	9	1.2	70	26	10	20	AS7-5512a
M-07-33	G34914	454	456	0.54	0.02	5	1.2	70	28	0.1	15	AS7-5512a
M-07-33	G34915	456	458	1.16	0.02	8	3.1	105	78	15	39	AS7-5512a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-33	G34916	458	460	0.32	0.01	5	1.6	65	32	15	31	AS7-5512a
M-07-33	G34917	460	462	0.61	0.03	7	1.8	95	58	10	40	AS7-5512a
M-07-33	G34918	462	464	0.48	0.04	10	1.4	50	40	20	43	AS7-5512a
M-07-33	G34919	464	466	0.24	0.03	4	0.9	40	28	5	26	AS7-5512a
M-07-33	G34920	466	468	0.13	0.01	4	0.9	40	34	15	41	AS7-5512a
M-07-33	G34921	468	470	0.34	0.01	31	1.2	70	36	20	47	AS7-5512a
M-07-33	G34922	470	472	0.27	0.01	7	1	90	22	15	20	AS7-5512a
M-07-33	G34923	472	474	0.24	0.00	9	0.8	75	18	0.1	6	AS7-5512a
M-07-33	G34924	474	476	0.47	0.00	4	1.1	65	32	10	11	AS7-5512a
M-07-33	G34925	476	478	0.21	0.01	11	1.3	65	30	20	27	AS7-5512a
M-07-33	G34926	478	480	0.15	0.02	34	1.1	50	16	50	8	AS7-5512a
M-07-33	G34927	480	482	0.41	0.02	6	1.4	25	50	10	30	AS7-5512a
M-07-33	G34928	482	484	0.92	0.02	5	1	25	28	15	32	AS7-5512a
M-07-33	G34929	484	486	0.45	0.00	6	1.3	20	34	20	38	AS7-5512a
M-07-33	G34930	486	488	0.16	0.01	8	1.5	10	40	30	54	AS7-5512a
M-07-33	G34931	488	490	0.14	0.00	17	1.3	15	38	15	41	AS7-5512a
M-07-33	G34933	490	492	0.25	0.01	30	1.4	45	44	20	50	AS7-5512a
M-07-33	G34936	492	494	0.31	0.01	7	0.3	50	64	20	65	AS7-5514a
M-07-33	G34937	494	496	0.28	0.01	16	0.01	20	62	15	79	AS7-5514a
M-07-33	G34938	496	498	0.09	0.01	6	0.2	20	98	20	69	AS7-5514a
M-07-33	G34939	498	500	0.08	0.00	4	0.2	25	72	15	79	AS7-5514a
M-07-33	G34941	500	502	0.05	0.00	4	0.01	20	46	15	56	AS7-5514a
M-07-33	G34942	502	504	0.08	0.01	6	0.01	20	48	15	37	AS7-5514a
M-07-33	G34943	504	506	0.47	0.01	12	0.4	25	74	0.1	33	AS7-5514a
M-07-33	G34944	506	508	0.13	0.00	17	0.01	25	56	10	48	AS7-5514a
M-07-33	G34945	508	510	0.08	0.00	39	0.2	25	78	15	51	AS7-5514a
M-07-33	G34946	510	512	0.26	0.00	63	1.1	55	98	30	61	AS7-5514a
M-07-33	G34947	512	514	0.20	0.01	9	0.2	30	38	10	24	AS7-5514a
M-07-33	G34948	514	516	0.47	0.01	7	0.3	25	26	20	19	AS7-5514a
M-07-33	G34949	516	518	0.38	0.01	17	0.5	55	72	45	62	AS7-5514a
M-07-33	G34951	518	520	0.20	0.01	8	0.2	30	44	25	38	AS7-5514a
M-07-33	G34952	520	522	0.38	0.00	10	0.7	70	68	0.1	26	AS7-5514a
M-07-33	G34953	522	524	0.20	0.01	8	0.4	10	64	10	73	AS7-5514a
M-07-33	G34954	524	526	0.14	0.01	10	0.6	20	48	0.1	42	AS7-5514a
M-07-33	G34955	526	528	0.18	0.01	22	0.3	30	40	15	45	AS7-5514a
M-07-33	G34956	528	530	0.12	0.00	34	0.4	50	28	65	26	AS7-5514a
M-07-33	G34957	530	532	0.31	0.02	15	0.4	55	16	40	28	AS7-5514a
M-07-33	G34958	532	534	0.41	0.03	15	0.4	30	24	15	31	AS7-5514a
M-07-33	G34959	534	536	0.30	0.00	36	0.2	15	42	20	54	AS7-5514a
M-07-33	G34960	536	538	0.31	0.01	34	0.4	35	58	15	50	AS7-5514a
M-07-33	G34961	538	540	0.30	0.00	10	0.3	25	38	10	46	AS7-5514a
M-07-33	G34962	540	542	0.29	0.00	4	0.8	35	54	0.1	10	AS7-5514a
M-07-33	G34963	542	544	0.88	0.00	7	0.8	30	68	0.1	27	AS7-5514a
M-07-33	G34964	544	546	1.21	0.01	5	1	35	44	25	56	AS7-5514a
M-07-33	G34965	546	548	0.77	0.00	7	0.6	40	48	0.1	21	AS7-5514a
M-07-33	G34966	548	550	0.51	0.00	5	0.5	50	30	0.1	10	AS7-5514a
M-07-33	G34967	550	552	0.77	0.01	7	0.7	30	30	0.1	23	AS7-5514a
M-07-33	G34968	552	554	0.64	0.00	7	0.7	35	26	10	26	AS7-5514a
M-07-33	G34969	554	556	0.25	0.00	17	0.4	50	22	0.1	14	AS7-5514a
M-07-33	G34970	556	558	0.40	0.00	9	0.7	65	36	0.1	31	AS7-5514a
M-07-33	G34971	558	560	1.33	0.01	4	0.7	35	36	10	45	AS7-5527a
M-07-33	G34972	560	562	0.40	0.00	4	0.4	40	26	10	23	AS7-5527a
M-07-33	G34973	562	564	0.45	0.00	6	0.6	45	28	0.1	11	AS7-5527a
M-07-33	G34974	564	566	0.40	0.00	7	1.9	35	554	15	455	AS7-5527a
M-07-33	G34975	566	568	0.84	0.00	4	1.1	60	34	0.1	58	AS7-5527a
M-07-33	G34976	568	570	1.05	0.01	0.1	1.2	75	32	0.1	66	AS7-5527a
M-07-33	G34977	570	572	0.81	0.00	2	1.4	40	26	10	25	AS7-5527a
M-07-33	G34978	572	574.22	0.22	0.00	2	0.7	45	46	0.1	18	AS7-5527a
M-07-34	G36844	1.5	3.5	1.30	0.35	13	4.6	40	30	0.1	105	AS7-5505a
M-07-34	G36845	3.5	5.5	0.86	0.22	12	3.3	60	26	5	96	AS7-5505a
M-07-34	G36846	5.5	7.5	0.81	0.22	13	4	115	26	15	135	AS7-5505a
M-07-34	G36847	7.5	9	0.75	0.17	14	3.5	40	32	0.1	109	AS7-5505a
M-07-34	G36848	9	10.4	0.84	0.17	25	3.7	45	50	0.1	108	AS7-5505a
M-07-34	G36849	10.4	12	0.82	0.17	23	3.2	40	46	0.1	159	AS7-5505a
M-07-34	G36850	12	14	1.09	0.25	20	4.6	35	44	0.1	214	AS7-5505a
M-07-34	G36851	14	16	1.21	0.28	20	4.1	35	56	0.1	196	AS7-5506a
M-07-34	G36852	16	18	0.65	0.17	18	1.9	20	68	0.1	267	AS7-5506a
M-07-34	G36853	18	20	0.79	0.15	23	3.1	60	38	0.1	165	AS7-5506a
M-07-34	G36855	20	22	0.72	0.16	26	3.7	45	40	0.1	230	AS7-5506a
M-07-34	G36856	22	24	0.79	0.19	23	2.9	35	54	0.1	143	AS7-5506a
M-07-34	G36857	24	26	0.93	0.21	21	3.1	45	42	0.1	167	AS7-5506a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-34	G36858	26	28	0.66	0.14	26	2.5	35	42	0.1	233	AS7-5506a
M-07-34	G36859	28	28.9	0.68	0.15	20	2.7	50	32	0.1	174	AS7-5506a
M-07-34	G36860	28.9	30.05	0.00	0.00	1	0.5	60	24	0.1	216	AS7-5506a
M-07-34	G36861	30.05	32	0.97	0.17	40	3.8	170	50	30	255	AS7-5506a
M-07-34	G36862	32	34	1.01	0.18	28	3.2	80	40	10	152	AS7-5506a
M-07-34	G36863	34	36	1.41	0.22	27	6.9	95	78	10	523	AS7-5506a
M-07-34	G36864	36	38.2	0.77	0.18	17	4.7	45	20	0.1	43	AS7-5506a
M-07-34	G36865	38.2	40	0.93	0.20	25	3	20	20	0.1	86	AS7-5506a
M-07-34	G36866	40	40.84	1.05	0.30	14	4	35	32	0.1	131	AS7-5506a
M-07-34	G36867	42	44	0.87	0.24	17	3.1	25	22	0.1	111	AS7-5506a
M-07-34	G36868	44	46	1.23	0.29	17	3.5	25	24	0.1	80	AS7-5506a
M-07-34	G36869	46	48	0.76	0.24	19	2.8	15	18	0.1	42	AS7-5506a
M-07-34	G36871	48	50	0.62	0.14	24	2.4	35	14	0.1	48	AS7-5506a
M-07-34	G36873	50	52	0.75	0.20	29	2.7	25	26	0.1	61	AS7-5506a
M-07-34	G36874	52	54	0.74	0.25	20	2.8	85	30	10	64	AS7-5506a
M-07-34	G36875	54	56	0.83	0.30	15	2.4	60	18	0.1	86	AS7-5506a
M-07-34	G36876	56	58	1.45	0.36	13	3	50	22	5	72	AS7-5506a
M-07-34	G36877	58	60	0.95	0.29	25	2.7	25	20	0.1	69	AS7-5506a
M-07-34	G36878	60	62	0.93	0.23	15	2.1	30	16	0.1	74	AS7-5506a
M-07-34	G36879	62	64	0.81	0.24	15	2	25	16	0.1	80	AS7-5506a
M-07-34	G36880	64	66	0.66	0.23	14	2.1	20	16	0.1	70	AS7-5506a
M-07-34	G36881	66	68	0.65	0.19	20	2	20	16	0.1	65	AS7-5506a
M-07-34	G36882	68	70	0.78	0.23	16	2.6	15	18	0.1	79	AS7-5506a
M-07-34	G36883	70	72	1.13	0.36	20	3.1	20	16	0.1	65	AS7-5506a
M-07-34	G36884	72	74	0.67	0.20	14	2	20	16	0.1	77	AS7-5506a
M-07-34	G36885	74	76	1.24	0.42	14	3.7	25	22	0.1	54	AS7-5506a
M-07-34	G36886	76	78	0.76	0.24	18	3.6	10	22	0.1	41	AS7-5510a
M-07-34	G36887	78	80	0.45	0.17	22	2.4	5	24	0.1	46	AS7-5510a
M-07-34	G36888	80	82	0.60	0.27	12	3.2	5	30	0.1	56	AS7-5510a
M-07-34	G36889	82	84	0.63	0.22	14	3	10	30	0.1	60	AS7-5510a
M-07-34	G36890	84	86	0.76	0.29	19	3.4	0.1	30	10	62	AS7-5510a
M-07-34	G36891	86	88	0.66	0.23	10	2.9	5	24	0.1	36	AS7-5510a
M-07-34	G36892	88	90	0.84	0.33	14	3.8	10	28	0.1	57	AS7-5510a
M-07-34	G36893	90	92	0.47	0.17	15	3	10	32	15	66	AS7-5510a
M-07-34	G36894	92	93.25	0.81	0.26	24	3.6	5	30	0.1	37	AS7-5510a
M-07-34	G36895	93.25	95	0.91	0.24	12	3.1	10	30	15	61	AS7-5510a
M-07-34	G36897	95	97	0.73	0.24	24	3.3	10	32	0.1	51	AS7-5510a
M-07-34	G36898	97	99	0.47	0.14	18	2.3	15	30	5	70	AS7-5510a
M-07-34	G36899	99	101	0.34	0.12	30	2.2	10	34	5	72	AS7-5510a
M-07-34	G36900	101	103	0.44	0.15	19	2.3	0.1	32	0.1	63	AS7-5510a
M-07-34	G36901	103	105	0.65	0.21	18	2.9	10	28	0.1	54	AS7-5510a
M-07-34	G36902	105	107	0.49	0.11	21	2.2	0.1	28	0.1	58	AS7-5510a
M-07-34	G36903	107	109	0.27	0.12	27	2.2	0.1	32	0.1	77	AS7-5510a
M-07-34	G36904	109	111	0.49	0.15	14	2.5	5	38	0.1	64	AS7-5510a
M-07-34	G36905	111	113	0.50	0.17	24	2.7	10	38	10	66	AS7-5510a
M-07-34	G36906	113	115	0.49	0.15	14	4.1	15	52	10	58	AS7-5510a
M-07-34	G36907	115	117	0.69	0.17	19	6.1	10	38	5	44	AS7-5510a
M-07-34	G36908	117	119	0.29	0.12	20	2.9	0.1	38	15	73	AS7-5510a
M-07-34	G36909	119	121	0.40	0.15	22	3.4	10	38	0.1	71	AS7-5510a
M-07-34	G36911	121	123	0.68	0.21	53	5	15	60	0.1	44	AS7-5510a
M-07-34	G36912	123	124.5	0.61	0.19	34	2.8	10	38	0.1	18	AS7-5510a
M-07-34	G36913	124.5	126.79	0.66	0.16	17	3.1	10	42	0.1	83	AS7-5510a
M-07-34	G36914	126.79	128.01	0.06	0.02	10	1.9	20	68	25	66	AS7-5510a
M-07-34	G36915	128.01	129.69	0.24	0.12	85	2.7	20	70	0.1	58	AS7-5510a
M-07-34	G36916	129.69	131.36	0.49	0.04	11	2.3	25	70	35	79	AS7-5510a
M-07-34	G36917	131.36	133	0.34	0.14	27	2.6	10	78	0.1	78	AS7-5510a
M-07-34	G36918	133	135	0.36	0.12	45	2.2	15	64	25	90	AS7-5510a
M-07-34	G36919	135	137	0.67	0.18	38	2.4	5	32	5	59	AS7-5510a
M-07-34	G36920	137	139	0.50	0.17	58	2.2	10	24	0.1	44	AS7-5510a
M-07-34	G36921	139	141	0.44	0.14	60	1.5	5	22	0.1	59	AS7-5516a
M-07-34	G36922	141	143	0.67	0.17	59	2	95	22	0.1	50	AS7-5516a
M-07-34	G36923	143	145	0.66	0.17	27	2.1	50	30	5	76	AS7-5516a
M-07-34	G36924	145	147	0.63	0.18	34	2.2	15	32	0.1	71	AS7-5516a
M-07-34	G36926	147	149	0.63	0.19	27	3	25	38	0.1	75	AS7-5516a
M-07-34	G36927	149	151.15	0.58	0.17	34	2.3	20	36	10	106	AS7-5516a
M-07-34	G36928	151.15	153	0.86	0.11	30	2	25	52	0.1	108	AS7-5516a
M-07-34	G36929	153	155	0.58	0.11	33	1.5	30	84	10	128	AS7-5516a
M-07-34	G36930	155	156.05	0.24	0.09	50	0.9	10	30	0.1	61	AS7-5516a
M-07-34	G36931	156.05	158	0.19	0.06	72	0.8	15	24	15	70	AS7-5516a
M-07-34	G36932	158	160	0.33	0.10	131	1.6	5	26	0.1	70	AS7-5516a
M-07-34	G36933	160	162	0.35	0.07	52	0.8	15	30	0.1	95	AS7-5516a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-34	G36934	162	164	0.59	0.11	75	1.2	10	32	5	82	AS7-5516a
M-07-34	G36935	164	166	0.42	0.11	69	1.1	10	28	0.1	71	AS7-5516a
M-07-34	G36937	166	168	0.33	0.07	61	1.1	10	28	10	76	AS7-5516a
M-07-34	G36938	168	170	0.38	0.07	46	1	15	28	0.1	68	AS7-5516a
M-07-34	G36939	170	172	0.33	0.07	65	0.8	15	32	0.1	81	AS7-5516a
M-07-34	G36940	172	174	0.27	0.07	49	1	0.1	30	5	103	AS7-5516a
M-07-34	G36941	174	176	0.31	0.09	44	1.3	20	38	0.1	83	AS7-5516a
M-07-34	G36942	176	178	0.24	0.05	32	0.8	15	26	15	108	AS7-5516a
M-07-34	G36943	178	180	0.29	0.08	44	1.4	10	38	0.1	87	AS7-5516a
M-07-34	G36944	180	182	0.51	0.21	41	2.6	15	30	0.1	88	AS7-5516a
M-07-34	G36945	182	184	0.54	0.21	32	2.4	0.1	26	0.1	58	AS7-5516a
M-07-34	G36946	184	186	0.59	0.15	39	1.8	0.1	38	0.1	51	AS7-5516a
M-07-34	G36947	186	188	0.39	0.10	136	1.2	10	30	10	76	AS7-5516a
M-07-34	G36948	188	190	0.28	0.08	28	1.1	10	48	10	117	AS7-5516a
M-07-34	G36950	190	192	0.55	0.15	52	1.7	15	50	15	143	AS7-5516a
M-07-34	G36951	192	194	0.99	0.32	103	2.8	5	58	10	128	AS7-5516a
M-07-34	G36952	194	196	0.33	0.09	41	1	20	68	0.1	109	AS7-5516a
M-07-34	G36953	196	198	0.28	0.09	40	1.1	15	50	15	115	AS7-5516a
M-07-34	G36954	198	200	0.56	0.13	150	1.4	15	46	5	114	AS7-5516a
M-07-34	G36955	200	202	0.36	0.10	52	1.2	10	74	10	155	AS7-5516a
M-07-34	G36956	202	204	0.33	0.08	69	1	25	104	0.1	229	AS7-5517a
M-07-34	G36957	204	206	0.46	0.11	43	1	40	62	10	192	AS7-5517a
M-07-34	G36958	206	208	0.43	0.10	86	1.1	30	70	0.1	159	AS7-5517a
M-07-34	G36959	208	210	0.59	0.15	61	1.8	30	430	10	379	AS7-5517a
M-07-34	G36960	210	212	0.40	0.15	56	1.7	20	54	5	166	AS7-5517a
M-07-34	G36961	212	214	0.32	0.09	60	1.2	35	50	15	155	AS7-5517a
M-07-34	G36963	214	216	0.40	0.13	73	1.4	35	44	5	79	AS7-5517a
M-07-34	G36964	216	218	0.32	0.13	46	1.6	30	44	10	81	AS7-5517a
M-07-34	G36965	218	220	0.44	0.17	107	1.9	30	44	10	94	AS7-5517a
M-07-34	G36966	220	222	0.45	0.14	231	1.9	30	68	5	121	AS7-5517a
M-07-34	G36967	222	224	0.29	0.15	94	1.8	35	76	15	145	AS7-5517a
M-07-34	G36968	224	226	0.35	0.14	196	2.2	35	48	5	149	AS7-5517a
M-07-34	G36969	226	228	0.38	0.15	100	2	25	42	5	132	AS7-5517a
M-07-34	G36970	228	230	0.94	0.17	52	2.3	25	38	5	199	AS7-5517a
M-07-34	G36971	230	232	0.36	0.10	62	1.2	15	36	10	139	AS7-5517a
M-07-34	G36973	232	234	0.62	0.20	45	2.5	25	34	5	232	AS7-5517a
M-07-34	G36974	234	236	0.45	0.11	59	1.6	25	44	5	154	AS7-5517a
M-07-34	G36975	236	238	0.41	0.15	47	1.5	20	42	0.1	197	AS7-5517a
M-07-34	G36976	238	240	0.52	0.17	74	2.1	35	58	5	121	AS7-5517a
M-07-34	G36977	240	242	0.75	0.22	416	2.5	30	46	0.1	126	AS7-5517a
M-07-34	G36978	242	244	0.65	0.15	102	1.8	20	84	10	167	AS7-5517a
M-07-34	G36979	244	246	0.40	0.14	71	1.5	25	38	5	150	AS7-5517a
M-07-34	G36980	246	248	0.19	0.06	29	1	25	42	0.1	122	AS7-5517a
M-07-34	G36981	248	250	0.31	0.12	48	1.5	30	70	5	196	AS7-5517a
M-07-34	G36982	250	252	0.52	0.14	87	1.4	25	34	5	74	AS7-5517a
M-07-34	G36984	252	254	0.49	0.13	54	1.6	35	40	5	94	AS7-5517a
M-07-34	G36985	254	256	0.65	0.15	96	1.6	35	40	0.1	90	AS7-5517a
M-07-34	G36986	256	257.4	0.30	0.10	54	1.4	35	36	0.1	75	AS7-5517a
M-07-34	G36987	257.4	258.76	0.69	0.12	140	2	35	606	0.1	504	AS7-5517a
M-07-34	G36988	258.76	260	0.67	0.23	83	2.9	35	48	0.1	58	AS7-5517a
M-07-34	G36989	260	262	0.45	0.14	107	1.7	30	32	10	67	AS7-5517a
M-07-34	G36990	262	264	0.47	0.15	64	1.8	30	34	0.1	62	AS7-5517a
M-07-34	G36991	264	266	0.49	0.14	57	2.1	0.1	2698	10	2833	AS7-5518a
M-07-34	G36992	266	268	0.89	0.21	70	2.4	25	28	0.1	43	AS7-5518a
M-07-34	G36993	268	270	0.63	0.19	116	2.2	10	26	10	45	AS7-5518a
M-07-34	G36994	270	272	1.04	0.29	213	2.6	15	26	0.1	33	AS7-5518a
M-07-34	G36995	272	274	0.74	0.19	101	1.6	0.1	58	5	52	AS7-5518a
M-07-34	G36996	274	276	0.41	0.13	61	1.2	10	28	0.1	62	AS7-5518a
M-07-34	G36997	276	278	0.55	0.18	44	2.1	10	26	0.1	53	AS7-5518a
M-07-34	G36998	278	280	0.52	0.19	43	2	15	28	10	46	AS7-5518a
M-07-34	G36999	280	282	0.39	0.13	22	2.3	20	34	0.1	74	AS7-5518a
M-07-34	G37000	282	284	0.46	0.14	109	2.1	20	30	10	56	AS7-5518a
M-07-34	G37002	284	286	0.43	0.12	31	2	10	24	0.1	53	AS7-5518a
M-07-34	G37003	286	288	0.34	0.13	52	2.1	10	26	0.1	44	AS7-5518a
M-07-34	G37004	288	290	0.52	0.14	56	1.6	10	28	10	47	AS7-5518a
M-07-34	G37005	290	292	0.49	0.16	67	2	25	26	10	49	AS7-5518a
M-07-34	G37006	292	294	0.48	0.13	40	1.6	30	24	10	46	AS7-5518a
M-07-34	G37007	294	296	0.39	0.11	60	1.5	20	24	0.1	54	AS7-5518a
M-07-34	G37008	296	298	0.35	0.10	32	1.1	15	28	0.1	61	AS7-5518a
M-07-34	G37009	298	300	0.27	0.07	24	0.8	20	26	10	66	AS7-5518a
M-07-34	G37010	300	302	0.34	0.09	33	1.2	10	24	10	56	AS7-5518a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-34	G37011	302	304	0.30	0.11	25	2.6	20	24	0.1	55	AS7-5518a
M-07-34	G37012	304	306	0.53	0.17	88	3	20	28	20	55	AS7-5518a
M-07-34	G37013	306	308	0.54	0.15	195	2.7	30	48	5	83	AS7-5518a
M-07-34	G37014	308	310	0.36	0.12	39	1.8	10	28	10	80	AS7-5518a
M-07-34	G37015	310	312	0.41	0.12	32	1.2	15	30	5	67	AS7-5518a
M-07-34	G37016	312	314	0.30	0.10	37	1.3	15	30	10	60	AS7-5518a
M-07-34	G37017	314	316	0.58	0.17	85	4.2	25	32	10	65	AS7-5518a
M-07-34	G37018	316	318	0.79	0.32	83	20.3	35	120	10	214	AS7-5518a
M-07-34	G37019	318	320	0.79	0.22	44	10.3	35	102	5	116	AS7-5518a
M-07-34	G37020	320	322	0.48	0.15	42	6.3	30	74	10	113	AS7-5518a
M-07-34	G37021	322	324	0.32	0.09	105	2.1	25	34	10	79	AS7-5518a
M-07-34	G37023	324	326	0.46	0.12	63	2.1	20	30	20	65	AS7-5518a
M-07-34	G37024	326	328	0.33	0.09	76	1.6	30	32	10	71	AS7-5518a
M-07-34	G37025	328	330	0.33	0.08	46	1.5	20	28	5	64	AS7-5518a
M-07-34	G37026	330	332	0.81	0.18	165	2.2	15	34	5	71	AS7-5526a
M-07-34	G37027	332	334	0.43	0.13	63	1.5	15	34	5	74	AS7-5526a
M-07-34	G37028	334	336	0.38	0.11	73	1.4	15	32	0.1	73	AS7-5526a
M-07-34	G37029	336	338	0.51	0.15	61	2	30	36	5	87	AS7-5526a
M-07-34	G37030	338	340	0.41	0.18	79	3.1	25	88	10	88	AS7-5526a
M-07-34	G37031	340	342	0.51	0.14	80	3	30	248	5	108	AS7-5526a
M-07-34	G37032	342	344	0.36	0.20	75	6.8	20	1232	0.1	2338	AS7-5526a
M-07-34	G37033	344	346	0.59	0.33	120	5.2	30	66	15	130	AS7-5526a
M-07-34	G37034	346	348	0.46	0.14	59	2.5	30	36	10	126	AS7-5526a
M-07-34	G37035	348	350	0.33	0.13	102	2.5	35	64	10	188	AS7-5526a
M-07-34	G37037	350	352	0.62	0.16	74	2.9	20	32	5	98	AS7-5526a
M-07-34	G37038	352	354	0.67	0.20	128	2.8	30	32	10	99	AS7-5526a
M-07-34	G37039	354	356	0.88	0.40	429	4.7	25	36	10	70	AS7-5526a
M-07-34	G37040	356	358	0.45	0.14	71	1.8	35	38	10	99	AS7-5526a
M-07-34	G37041	358	360	0.37	0.11	50	1.9	25	36	10	100	AS7-5526a
M-07-34	G37042	360	362	0.70	0.09	92	1.5	35	30	5	72	AS7-5526a
M-07-34	G37043	362	364	0.36	0.09	137	1.4	35	30	0.1	64	AS7-5526a
M-07-34	G37044	364	366	0.59	0.20	175	3.7	25	60	5	87	AS7-5526a
M-07-34	G37045	366	368	0.36	0.07	18	2	25	36	5	81	AS7-5526a
M-07-34	G37046	368	370	0.26	0.07	35	1.1	15	34	5	92	AS7-5526a
M-07-34	G37047	370	372	0.55	0.12	40	1.4	10	30	0.1	130	AS7-5526a
M-07-34	G37048	372	374	0.25	0.06	169	0.6	10	28	5	85	AS7-5526a
M-07-34	G37049	374	376	0.44	0.15	78	1.5	15	32	10	69	AS7-5526a
M-07-34	G37050	376	378	0.25	0.08	86	0.7	20	46	5	69	AS7-5526a
M-07-34	G37051	378	380	0.41	0.11	50	1.3	20	32	5	61	AS7-5526a
M-07-34	G37052	380	382	0.54	0.12	108	1.4	20	30	10	57	AS7-5526a
M-07-34	G37054	382	384	0.37	0.13	121	2.2	25	36	20	80	AS7-5526a
M-07-34	G37055	384	386	0.40	0.11	78	3.3	20	38	5	88	AS7-5526a
M-07-34	G37056	386	388	0.68	0.08	31	3.2	15	34	15	97	AS7-5526a
M-07-34	G37057	388	390	0.31	0.12	62	1.4	25	38	10	84	AS7-5526a
M-07-34	G37058	390	392	0.18	0.09	65	0.8	30	42	15	89	AS7-5526a
M-07-34	G37059	392	394	0.46	0.12	86	1.5	35	48	10	86	AS7-5526a
M-07-34	G37060	394	396	0.27	0.07	148	0.6	25	34	0.1	57	AS7-5526a
M-07-34	G37061	396	398	0.40	0.07	62	0.9	25	34	10	69	AS7-5531a
M-07-34	G37062	398	400	0.18	0.06	38	0.5	0.1	22	0.1	74	AS7-5531a
M-07-34	G37063	400	402	0.22	0.06	29	0.8	0.1	24	10	99	AS7-5531a
M-07-34	G37064	402	404	0.27	0.05	37	0.7	20	20	5	90	AS7-5531a
M-07-34	G37065	404	406	0.14	0.06	50	0.8	10	22	10	106	AS7-5531a
M-07-34	G37066	406	408	0.20	0.10	170	1	5	30	10	77	AS7-5531a
M-07-34	G37067	408	410	0.20	0.06	28	0.8	5	30	10	98	AS7-5531a
M-07-34	G37068	410	412	0.34	0.12	64	4.6	30	196	0.1	159	AS7-5531a
M-07-34	G37069	412	414	0.22	0.06	53	4.7	15	100	0.1	336	AS7-5531a
M-07-34	G37070	414	416	0.17	0.06	154	1.5	30	26	5	94	AS7-5531a
M-07-34	G37071	416	418	0.43	0.13	171	2.2	25	24	15	81	AS7-5531a
M-07-34	G37072	418	420	0.30	0.09	110	1.5	25	28	5	107	AS7-5531a
M-07-34	G37073	420	422	0.44	0.11	61	1.6	20	30	15	67	AS7-5531a
M-07-34	G37075	422	424	0.21	0.07	44	1.1	5	28	10	82	AS7-5531a
M-07-34	G37076	424	426	0.18	0.07	52	1	10	30	15	82	AS7-5531a
M-07-34	G37077	426	428	0.36	0.07	81	1.7	20	80	0.1	209	AS7-5531a
M-07-34	G37078	428	430	0.26	0.11	117	2.3	25	118	5	1511	AS7-5531a
M-07-34	G37079	430	432	0.19	0.10	41	1.6	30	64	5	86	AS7-5531a
M-07-34	G37080	432	434	0.14	0.06	144	0.9	35	54	10	129	AS7-5531a
M-07-34	G37081	434	436	0.11	0.02	28	0.4	20	22	0.1	64	AS7-5531a
M-07-34	G37082	436	438	0.19	0.04	60	0.5	30	30	20	79	AS7-5531a
M-07-34	G37083	438	440	0.17	0.05	22	0.7	25	28	15	83	AS7-5531a
M-07-34	G37084	440	442	0.10	0.04	113	0.7	15	26	10	68	AS7-5531a
M-07-34	G37085	442	444	0.09	0.04	24	0.4	20	24	10	74	AS7-5531a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-34	G37086	444	446	0.13	0.05	147	0.7	15	28	10	62	AS7-5531a
M-07-34	G37087	446	448	0.12	0.04	20	0.6	20	26	15	72	AS7-5531a
M-07-34	G37088	448	450	0.14	0.06	81	2.5	40	90	0.1	146	AS7-5531a
M-07-34	G37090	450	452	0.18	0.08	105	1.4	25	44	0.1	64	AS7-5531a
M-07-34	G37091	452	454	0.17	0.08	58	1	25	34	0.1	60	AS7-5531a
M-07-34	G37092	454	456	0.09	0.05	51	0.6	25	34	20	74	AS7-5531a
M-07-34	G37093	456	458	0.12	0.06	24	0.9	25	72	20	58	AS7-5531a
M-07-34	G37094	458	460	0.16	0.06	35	0.9	30	34	10	80	AS7-5531a
M-07-34	G37095	460	462	0.09	0.08	103	1.1	25	44	10	84	AS7-5531a
M-07-34	G37096	462	464	0.10	0.08	88	1.6	30	44	15	78	AS7-5532a
M-07-34	G37097	464	466	0.06	0.05	44	1.2	20	36	10	116	AS7-5532a
M-07-34	G37098	466	468	0.16	0.07	71	4.9	25	96	10	182	AS7-5532a
M-07-34	G37099	468	470	0.11	0.05	62	3.1	20	38	10	93	AS7-5532a
M-07-34	G37100	470	472	0.11	0.05	64	2.3	25	34	10	102	AS7-5532a
M-07-34	G37101	472	474	0.72	0.07	93	3.2	40	118	5	401	AS7-5532a
M-07-34	G37103	474	476	0.11	0.04	29	1.7	25	32	20	115	AS7-5532a
M-07-34	G37104	476	478	0.06	0.04	22	1.1	35	30	5	109	AS7-5532a
M-07-34	G37105	478	480	0.06	0.05	36	1.4	25	34	10	98	AS7-5532a
M-07-34	G37106	480	482	0.08	0.05	54	1.8	30	42	10	137	AS7-5532a
M-07-34	G37107	482	484	0.16	0.05	38	1.6	25	40	0.1	122	AS7-5532a
M-07-34	G37108	484	485.5	0.13	0.05	105	1.3	20	40	10	70	AS7-5532a
M-07-34	G37109	485.5	486.44	0.11	0.03	34	0.8	15	30	5	63	AS7-5532a
M-07-35	G34979	6.3	8	0.41	0.08	73	1	35	40	10	50	AS7-5527a
M-07-35	G34980	8	10	0.68	0.09	78	1.8	20	60	15	56	AS7-5527a
M-07-35	G34981	10	12	0.31	0.06	45	0.6	20	42	10	60	AS7-5527a
M-07-35	G34982	12	14	0.82	0.06	110	2.1	45	50	10	44	AS7-5527a
M-07-35	G34983	14	16	0.29	0.04	54	0.5	35	52	15	72	AS7-5527a
M-07-35	G34984	16	18	0.32	0.05	32	0.4	25	52	15	53	AS7-5527a
M-07-35	G34985	18	20	0.30	0.07	55	0.8	30	40	25	67	AS7-5527a
M-07-35	G34986	20	22	1.55	0.06	86	3.2	130	46	65	68	AS7-5527a
M-07-35	G34987	22	24	0.53	0.05	136	4.3	65	44	35	65	AS7-5527a
M-07-35	G34988	24	26	2.54	0.03	67	5.8	110	56	45	70	AS7-5527a
M-07-35	G34989	26	28	0.32	0.07	109	32.6	145	1480	125	574	AS7-5527a
M-07-35	G34991	28	30	0.40	0.04	102	4.4	85	102	45	112	AS7-5527a
M-07-35	G34992	30	32	0.34	0.04	57	1.5	50	94	25	209	AS7-5527a
M-07-35	G34993	32	34	0.15	0.05	73	1	20	80	20	63	AS7-5527a
M-07-35	G34994	34	36	0.19	0.07	130	1.6	35	76	10	90	AS7-5527a
M-07-35	G34995	36	38	0.19	0.05	53	0.8	35	64	20	132	AS7-5527a
M-07-35	G34998	38	40	0.24	0.05	44	0.7	30	58	15	73	AS7-5527a
M-07-35	G34999	40	42	0.23	0.05	63	0.6	30	54	10	66	AS7-5527a
M-07-35	G35000	42	44	0.26	0.06	110	1.3	30	56	15	67	AS7-5527a
M-07-35	G35001	44	46	0.22	0.05	73	0.9	40	56	30	82	AS7-5527a
M-07-35	G35002	46	48	0.26	0.05	73	2.8	60	96	30	162	AS7-5527a
M-07-35	G35003	48	50	0.31	0.07	85	1.3	45	86	20	145	AS7-5527a
M-07-35	G35004	50	52	0.22	0.04	272	0.8	35	66	10	85	AS7-5527a
M-07-35	G35005	52	54	0.38	0.08	95	1.4	45	98	20	92	AS7-5527a
M-07-35	G35006	54	56	0.35	0.09	178	1.2	15	62	20	72	AS7-5528a
M-07-35	G35007	56	58	0.28	0.06	160	0.8	15	60	10	76	AS7-5528a
M-07-35	G35008	58	60	0.48	0.11	268	1.3	15	66	10	93	AS7-5528a
M-07-35	G35009	60	62	0.35	0.09	65	1	25	54	15	99	AS7-5528a
M-07-35	G35010	62	64	0.48	0.09	165	1.4	25	74	10	79	AS7-5528a
M-07-35	G35011	64	66	0.53	0.10	135	1.2	15	84	10	106	AS7-5528a
M-07-35	G35012	66	68	0.41	0.07	86	1	15	60	10	107	AS7-5528a
M-07-35	G35013	68	70	0.23	0.05	41	0.7	15	52	15	115	AS7-5528a
M-07-35	G35014	70	72	0.22	0.06	38	0.9	30	60	0.1	81	AS7-5528a
M-07-35	G35015	72	74	0.37	0.06	76	0.7	5	54	15	68	AS7-5528a
M-07-35	G35016	74	76	0.33	0.07	201	0.8	15	52	30	75	AS7-5528a
M-07-35	G35017	76	78	0.61	0.12	115	7.2	15	272	15	85	AS7-5528a
M-07-35	G35018	78	80	0.56	0.13	288	8.3	70	76	40	131	AS7-5528a
M-07-35	G35019	80	82	0.65	0.13	88	9.2	55	158	30	155	AS7-5528a
M-07-35	G35020	82	84	0.42	0.10	55	3.4	10	50	5	91	AS7-5528a
M-07-35	G35021	84	86	0.56	0.13	88	8.1	45	70	25	134	AS7-5528a
M-07-35	G35022	86	88	1.03	0.20	17	3	10	66	0.1	65	AS7-5528a
M-07-35	G35023	88	90	1.73	0.19	33	10.8	90	140	35	103	AS7-5528a
M-07-35	G35024	90	92	1.12	0.39	52	6.4	105	232	40	268	AS7-5528a
M-07-35	G35025	92	94	1.06	0.33	17	4.1	35	54	10	61	AS7-5528a
M-07-35	G35026	94	96	0.75	0.17	36	2.4	25	72	5	202	AS7-5528a
M-07-35	G35027	96	98	0.56	0.12	22	1.6	10	26	10	61	AS7-5528a
M-07-35	G35028	98	100	0.70	0.16	19	2.3	10	48	5	62	AS7-5528a
M-07-35	G35029	100	102	0.74	0.16	15	2.4	0.1	48	0.1	253	AS7-5528a
M-07-35	G35031	102	104	0.63	0.18	19	2.2	15	30	0.1	95	AS7-5528a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-35	G35032	104	106	0.55	0.19	17	3.2	15	52	0.1	63	AS7-5528a
M-07-35	G35033	106	108	0.71	0.20	20	3.3	0.1	24	0.1	49	AS7-5528a
M-07-35	G35034	108	110	0.47	0.20	23	7.5	15	128	0.1	164	AS7-5528a
M-07-35	G35035	110	112	0.41	0.16	27	2.5	0.1	34	0.1	20	AS7-5528a
M-07-35	G35036	112	114	0.71	0.14	24	2.6	10	56	10	69	AS7-5528a
M-07-35	G35037	114	116	1.18	0.15	21	2.4	0.1	26	0.1	25	AS7-5528a
M-07-35	G35038	116	118	1.64	0.26	21	3.3	0.1	22	10	36	AS7-5528a
M-07-35	G35039	118	120	0.98	0.14	20	2.2	0.1	86	0.1	121	AS7-5528a
M-07-35	G35041	120	122	0.53	0.11	17	1.6	0.1	20	0.1	44	AS7-5530a
M-07-35	G35042	122	124	0.67	0.15	20	2.2	0.1	20	0.1	54	AS7-5530a
M-07-35	G35044	124	126	1.03	0.19	16	2.4	0.1	16	0.1	27	AS7-5530a
M-07-35	G35045	126	128	0.60	0.13	17	1.9	10	16	0.1	29	AS7-5530a
M-07-35	G35046	128	130	0.87	0.17	26	2.9	10	38	0.1	67	AS7-5530a
M-07-35	G35047	130	132	0.85	0.15	17	2.3	15	24	5	61	AS7-5530a
M-07-35	G35048	132	134	0.84	0.17	19	2.6	0.1	18	0.1	57	AS7-5530a
M-07-35	G35049	134	136	0.61	0.12	16	2.1	0.1	20	0.1	49	AS7-5530a
M-07-35	G35050	136	138	0.58	0.13	18	1.9	5	34	0.1	68	AS7-5530a
M-07-35	G35051	138	140	1.73	0.49	17	4.5	20	44	0.1	95	AS7-5530a
M-07-35	G35052	140	142	0.86	0.20	13	3.5	15	44	0.1	44	AS7-5530a
M-07-35	G35053	142	144	1.25	0.20	48	2.9	0.1	44	0.1	30	AS7-5530a
M-07-35	G35054	144	146	0.29	0.07	19	0.9	0.1	14	0.1	23	AS7-5530a
M-07-35	G35055	146	148	0.47	0.11	17	2.1	15	18	0.1	38	AS7-5530a
M-07-35	G35056	148	150	0.44	0.11	14	2	0.1	16	0.1	52	AS7-5530a
M-07-35	G35057	150	152	0.56	0.11	20	1.8	10	14	0.1	70	AS7-5530a
M-07-35	G35058	152	154	0.73	0.12	16	2.2	40	32	0.1	41	AS7-5530a
M-07-35	G35059	154	156	0.76	0.12	16	2.1	5	28	0.1	46	AS7-5530a
M-07-35	G35060	156	158	0.78	0.15	17	3.9	20	30	0.1	48	AS7-5530a
M-07-35	G35061	158	160	0.61	0.16	24	3	15	30	0.1	56	AS7-5530a
M-07-35	G35062	160	162	0.48	0.14	17	2.1	20	20	0.1	36	AS7-5530a
M-07-35	G35063	162	164	0.59	0.14	19	2.4	0.1	24	0.1	61	AS7-5530a
M-07-35	G35064	164	166	0.49	0.12	15	1.9	0.1	16	0.1	56	AS7-5530a
M-07-35	G35065	166	168	0.91	0.23	18	3.7	5	34	0.1	93	AS7-5530a
M-07-35	G35066	168	170	1.07	0.26	27	3.8	0.1	36	0.1	184	AS7-5530a
M-07-35	G35068	170	172	1.08	0.26	17	3.9	0.1	26	0.1	78	AS7-5530a
M-07-35	G35069	172	174	1.07	0.17	17	3.5	0.1	124	0.1	121	AS7-5530a
M-07-35	G35070	174	176	1.23	0.31	24	5	5	52	0.1	111	AS7-5530a
M-07-35	G35071	176	178	1.09	0.25	19	3.5	0.1	38	0.1	96	AS7-5530a
M-07-35	G35072	178	180	1.09	0.22	16	3.2	0.1	32	0.1	131	AS7-5530a
M-07-35	G35074	180	182	1.18	0.21	21	3.5	0.1	34	0.1	108	AS7-5530a
M-07-35	G35075	182	184	0.68	0.15	20	2.8	0.1	34	0.1	103	AS7-5530a
M-07-35	G35076	184	186	0.73	0.15	20	2.6	0.1	24	0.1	137	AS7-5533a
M-07-35	G35077	186	188	1.08	0.15	23	5.7	0.1	224	0.1	111	AS7-5533a
M-07-35	G35078	188	190	0.83	0.15	27	2.8	5	24	0.1	116	AS7-5533a
M-07-35	G35079	190	192	1.17	0.18	19	3.8	15	30	0.1	103	AS7-5533a
M-07-35	G35080	192	194	0.76	0.19	14	4.2	25	30	0.1	53	AS7-5533a
M-07-35	G35081	194	196	0.90	0.19	13	3.2	0.1	22	0.1	69	AS7-5533a
M-07-35	G35082	196	198	1.35	0.33	13	5.1	0.1	24	0.1	65	AS7-5533a
M-07-35	G35083	198	200	1.21	0.25	16	5.3	10	38	5	85	AS7-5533a
M-07-35	G35084	200	202	0.80	0.15	16	3.6	15	42	0.1	183	AS7-5533a
M-07-35	G35085	202	204	0.70	0.15	16	3.4	0.1	36	0.1	136	AS7-5533a
M-07-35	G35086	204	206	0.78	0.14	17	3	5	32	5	134	AS7-5533a
M-07-35	G35087	206	208	0.77	0.15	21	3.8	0.1	50	0.1	115	AS7-5533a
M-07-35	G35088	208	210	0.69	0.14	16	3.6	15	52	0.1	96	AS7-5533a
M-07-35	G35089	210	212	1.29	0.28	25	5.3	10	56	0.1	108	AS7-5533a
M-07-35	G35091	212	214	1.21	0.19	13	4.3	0.1	38	0.1	82	AS7-5533a
M-07-35	G35092	214	216	1.18	0.21	16	4	0.1	36	0.1	80	AS7-5533a
M-07-35	G35093	216	218	1.33	0.20	17	13.5	15	54	0.1	100	AS7-5533a
M-07-35	G35094	218	220	1.16	0.27	23	4.7	5	38	0.1	91	AS7-5533a
M-07-35	G35096	220	222	1.66	0.23	19	5	10	48	0.1	84	AS7-5533a
M-07-35	G35097	222	224	2.67	0.20	21	4.8	165	32	20	75	AS7-5533a
M-07-35	G35098	224	226	1.39	0.16	16	3.1	85	18	0.1	36	AS7-5533a
M-07-35	G35099	226	228	1.69	0.30	16	4.6	35	26	0.1	43	AS7-5533a
M-07-35	G35100	228	230	1.61	0.36	14	5	0.1	64	0.1	141	AS7-5533a
M-07-35	G35101	230	232	0.82	0.15	13	2.7	0.1	52	0.1	64	AS7-5533a
M-07-35	G35102	232	234	0.84	0.19	11	3.4	0.1	50	0.1	76	AS7-5533a
M-07-35	G35103	234	236	0.80	0.17	13	3.8	0.1	64	0.1	331	AS7-5533a
M-07-35	G35104	236	238	1.32	0.24	17	4.6	5	52	10	157	AS7-5533a
M-07-35	G35105	238	240	1.25	0.27	13	4.1	0.1	56	0.1	111	AS7-5533a
M-07-35	G35106	240	242	0.98	0.26	18	4.5	0.1	56	0.1	149	AS7-5533a
M-07-35	G35107	242	244	0.93	0.22	19	3.7	0.1	66	0.1	344	AS7-5533a
M-07-35	G35108	244	246	1.05	0.21	18	4	10	94	0.1	218	AS7-5533a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-35	G35109	246	248	1.06	0.19	17	2.8	0.1	30	0.1	101	AS7-5533a
M-07-35	G35110	248	250	1.30	0.31	13	5.2	40	54	0.1	89	AS7-5533a
M-07-35	G35112	250	252	0.97	0.14	13	2.7	60	30	0.1	77	AS7-5538a
M-07-35	G35113	252	254	1.10	0.17	12	3.1	35	24	0.1	25	AS7-5538a
M-07-35	G35114	254	256	2.35	0.32	21	4.4	15	46	0.1	90	AS7-5538a
M-07-35	G35115	256	258	1.51	0.21	13	3.2	15	26	0.1	70	AS7-5538a
M-07-35	G35116	258	260	2.78	0.31	20	4.2	0.1	72	0.1	110	AS7-5538a
M-07-35	G35117	260	262	1.02	0.19	14	2.5	10	30	0.1	17	AS7-5538a
M-07-35	G35118	262	264	1.06	0.27	16	2.8	20	22	0.1	26	AS7-5538a
M-07-35	G35119	264	266	1.06	0.28	13	3.4	0.1	48	0.1	197	AS7-5538a
M-07-35	G35120	266	267	1.01	0.36	13	3.9	5	42	0.1	39	AS7-5538a
M-07-35	G35121	267	269	1.36	0.21	13	2.6	20	26	0.1	22	AS7-5538a
M-07-35	G35122	269	271	0.75	0.28	13	4.3	0.1	34	0.1	20	AS7-5538a
M-07-35	G35124	271	273	1.56	0.27	14	10.2	160	54	45	103	AS7-5538a
M-07-35	G35125	273	275	2.39	0.29	12	17.2	115	58	25	189	AS7-5538a
M-07-35	G35126	275	277	2.30	0.35	16	7.6	60	182	0.1	283	AS7-5538a
M-07-35	G35127	277	279	1.60	0.28	14	8.7	50	214	10	257	AS7-5538a
M-07-35	G35128	279	280.4	1.71	0.27	19	5.3	30	66	0.1	39	AS7-5538a
M-07-35	G35129	280.4	282	1.54	0.24	14	3.1	15	32	0.1	62	AS7-5538a
M-07-35	G35130	282	283.55	2.72	0.36	16	4.3	25	50	0.1	102	AS7-5538a
M-07-35	G35131	283.55	285	1.24	0.42	12	5.7	10	142	0.1	185	AS7-5538a
M-07-35	G35132	285	287	1.93	0.36	14	8.3	30	90	10	218	AS7-5538a
M-07-35	G35133	287	289	0.91	0.28	14	26.5	210	332	110	365	AS7-5538a
M-07-35	G35134	289	291	1.12	0.34	16	6.2	25	60	0.1	123	AS7-5538a
M-07-35	G35135	291	293	1.35	0.26	13	3.4	15	38	0.1	54	AS7-5538a
M-07-35	G35136	293	295	1.41	0.31	16	3.8	25	30	0.1	83	AS7-5538a
M-07-35	G35137	295	297	1.16	0.32	15	3.8	10	52	0.1	80	AS7-5538a
M-07-35	G35138	297	299	0.57	0.23	16	3.3	0.1	124	0.1	120	AS7-5538a
M-07-35	G35139	299	301	1.33	0.22	21	3.2	20	52	0.1	108	AS7-5538a
M-07-35	G35140	301	303	1.24	0.20	17	3.1	15	52	0.1	79	AS7-5538a
M-07-35	G35141	303	304.9	1.63	0.25	15	7.1	40	68	0.1	95	AS7-5538a
M-07-35	G35142	304.9	306	1.07	0.24	15	4.1	20	102	0.1	98	AS7-5538a
M-07-35	G35143	306	308	0.72	0.21	15	5.4	20	92	0.1	142	AS7-5538a
M-07-35	G35144	308	310	0.30	0.21	15	19.9	110	40	115	409	AS7-5538a
M-07-35	G35146	310	312	0.39	0.21	18	69.3	80	450	160	361	AS7-5539a
M-07-35	G35147	312	314	1.05	0.38	16	227	200	1478	405	1893	AS7-5539a
M-07-35	G35148	314	315.8	0.45	0.34	17	100	125	620	435	1503	AS7-5539a
M-07-35	G35149	315.8	317.8	0.86	0.24	14	3.2	0.1	100	10	182	AS7-5539a
M-07-35	G35150	317.8	319.1	0.83	0.33	14	3.9	0.1	74	0.1	138	AS7-5539a
M-07-35	G35151	319.1	321	0.53	0.34	13	4.4	0.1	66	0.1	102	AS7-5539a
M-07-35	G35152	321	323	0.43	0.32	18	3.6	0.1	52	0.1	47	AS7-5539a
M-07-35	G35154	323	325	0.81	0.29	38	3.6	0.1	274	0.1	486	AS7-5539a
M-07-35	G35155	325	327	1.48	0.36	17	4.5	0.1	106	0.1	320	AS7-5539a
M-07-35	G35156	327	329	0.63	0.34	16	5.7	0.1	112	10	158	AS7-5539a
M-07-35	G35157	329	331	0.48	0.28	26	5.2	0.1	50	0.1	50	AS7-5539a
M-07-35	G35158	331	333	0.54	0.28	22	3.3	0.1	148	0.1	740	AS7-5539a
M-07-35	G35159	333	335	0.97	0.30	19	3.5	0.1	102	0.1	898	AS7-5539a
M-07-35	G35160	335	337	1.08	0.39	14	3.6	0.1	36	0.1	241	AS7-5539a
M-07-35	G35161	337	339	0.56	0.24	16	2.6	0.1	40	0.1	82	AS7-5539a
M-07-35	G35163	339	341	0.25	0.33	17	2.9	0.1	26	0.1	27	AS7-5539a
M-07-35	G35164	341	343	0.15	0.25	15	3.6	0.1	24	10	24	AS7-5539a
M-07-35	G35165	343	345	0.34	0.38	16	4.3	5	34	30	65	AS7-5539a
M-07-35	G35166	345	347	0.92	0.28	14	3.3	0.1	68	0.1	205	AS7-5539a
M-07-35	G35167	347	349	0.53	0.40	16	4.5	0.1	50	5	75	AS7-5539a
M-07-35	G35168	349	351	0.32	0.37	8	7.3	50	20	80	41	AS7-5539a
M-07-35	G35169	351	353	0.26	0.34	19	4.8	0.1	24	30	39	AS7-5539a
M-07-35	G35170	353	355	0.69	0.48	22	4.3	0.1	42	0.1	131	AS7-5539a
M-07-35	G35171	355	357	0.31	0.23	17	3.5	0.1	56	0.1	118	AS7-5539a
M-07-35	G35172	357	359	0.35	0.25	21	3.2	0.1	64	0.1	147	AS7-5539a
M-07-35	G35173	359	361	0.57	0.26	24	2.7	0.1	40	5	111	AS7-5539a
M-07-35	G35175	361	363	0.54	0.29	14	4.5	0.1	64	0.1	129	AS7-5539a
M-07-35	G35176	363	365	0.81	0.35	19	5.5	0.1	70	10	234	AS7-5539a
M-07-35	G35177	365	367	1.22	0.22	14	2.7	0.1	42	0.1	88	AS7-5539a
M-07-35	G35178	367	369	0.92	0.24	19	3	0.1	52	10	122	AS7-5539a
M-07-35	G35179	369	371	1.00	0.26	20	4.1	0.1	102	0.1	277	AS7-5539a
M-07-35	G35180	371	373	0.85	0.26	17	4	0.1	58	5	91	AS7-5539a
M-07-35	G35181	373	375	1.44	0.26	10	4.1	15	74	0.1	128	AS7-5544a
M-07-35	G35182	375	377	1.62	0.30	12	4.8	25	76	0.1	114	AS7-5544a
M-07-35	G35183	377	379	1.08	0.24	14	4.4	25	86	0.1	216	AS7-5544a
M-07-35	G35184	379	381	0.70	0.22	10	3.2	10	108	0.1	104	AS7-5544a
M-07-35	G35185	381	383	0.75	0.26	20	2.6	15	228	0.1	267	AS7-5544a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-35	G35186	383	385	1.81	0.27	22	3.4	30	66	0.1	134	AS7-5544a
M-07-35	G35187	385	387	2.15	0.27	16	7.7	30	72	0.1	111	AS7-5544a
M-07-35	G35188	387	389	1.15	0.29	28	5.6	20	66	15	159	AS7-5544a
M-07-35	G35189	389	391	1.20	0.29	13	3.3	5	70	0.1	80	AS7-5544a
M-07-35	G35190	391	392.2	0.76	0.33	10	3.9	10	82	0.1	69	AS7-5544a
M-07-35	G35192	392.2	393.4	0.71	0.25	14	3.7	10	66	0.1	128	AS7-5544a
M-07-35	G35193	393.4	395	0.96	0.24	14	2.8	10	52	0.1	52	AS7-5544a
M-07-35	G35194	395	397	0.95	0.26	12	3	10	54	0.1	29	AS7-5544a
M-07-35	G35195	397	399	0.98	0.22	18	3.4	40	28	0.1	85	AS7-5544a
M-07-35	G35196	399	401	0.48	0.32	43	5.7	10	32	0.1	15	AS7-5544a
M-07-35	G35197	401	403	0.73	0.17	13	4.6	75	24	10	23	AS7-5544a
M-07-35	G35198	403	405	1.33	0.54	8	12.9	270	34	40	42	AS7-5544a
M-07-35	G35199	405	407	1.47	0.16	9	3.4	70	32	10	41	AS7-5544a
M-07-35	G35200	407	409	0.68	0.18	26	3.6	40	26	5	28	AS7-5544a
M-07-35	G35202	409	411	0.56	0.26	12	5.1	55	24	10	28	AS7-5544a
M-07-35	G35203	411	413	1.59	0.29	11	3.4	15	28	0.1	70	AS7-5544a
M-07-35	G35204	413	414.5	0.69	0.31	11	3.1	5	34	0.1	98	AS7-5544a
M-07-35	G35205	414.5	415.85	0.42	0.29	13	3	0.1	58	0.1	169	AS7-5544a
M-07-35	G35206	415.85	417	1.02	0.16	11	1.9	50	34	0.1	102	AS7-5544a
M-07-35	G35207	417	419	0.96	0.27	21	2.8	20	54	0.1	49	AS7-5544a
M-07-35	G35208	419	421	1.10	0.17	19	1.8	40	34	0.1	66	AS7-5544a
M-07-35	G35209	421	423	0.89	0.21	17	2.1	30	22	0.1	70	AS7-5544a
M-07-35	G35210	423	425	0.94	0.25	11	2.2	15	30	0.1	80	AS7-5544a
M-07-35	G35211	425	427	0.64	0.17	9	1.4	5	20	0.1	60	AS7-5544a
M-07-35	G35212	427	429	0.65	0.23	19	2.8	5	26	0.1	63	AS7-5544a
M-07-35	G35213	429	431	0.56	0.27	11	4.9	45	42	5	67	AS7-5544a
M-07-35	G35215	431	433	1.00	0.20	10	2	20	20	0.1	77	AS7-5544a
M-07-35	G35216	433	435	0.76	0.29	12	2.7	15	20	0.1	51	AS7-5553a
M-07-35	G35217	435	437	0.47	0.34	12	3.1	10	28	0.1	37	AS7-5553a
M-07-35	G35218	437	439	0.95	0.22	42	1.9	10	20	0.1	41	AS7-5553a
M-07-35	G35220	439	441	0.37	0.16	12	2.3	10	58	0.1	79	AS7-5553a
M-07-35	G35221	441	443	0.53	0.36	24	25.3	70	66	30	330	AS7-5553a
M-07-35	G35222	443	445	0.37	0.16	18	2.2	5	36	0.1	80	AS7-5553a
M-07-35	G35223	445	447	0.67	0.14	14	1.3	10	14	0.1	52	AS7-5553a
M-07-35	G35224	447	449	0.61	0.17	16	1.5	10	14	0.1	28	AS7-5553a
M-07-35	G35225	449	451	1.78	0.16	20	1.6	10	20	0.1	56	AS7-5553a
M-07-35	G35226	451	453	0.46	0.25	11	2.3	10	34	0.1	84	AS7-5553a
M-07-35	G35227	453	455	1.11	0.23	12	2.3	10	22	0.1	30	AS7-5553a
M-07-35	G35228	455	457	1.45	0.55	20	5.9	15	96	0.1	1860	AS7-5553a
M-07-35	G35229	457	459	1.08	0.22	106	3	15	48	5	73	AS7-5553a
M-07-35	G35230	459	460.25	2.85	0.20	10	4.1	20	218	0.1	178	AS7-5553a
M-07-35	G35231	460.25	462	0.84	0.30	17	4.4	10	50	0.1	67	AS7-5553a
M-07-35	G35232	462	464	0.43	0.34	16	6.1	10	54	0.1	48	AS7-5553a
M-07-35	G35233	464	466	0.47	0.58	16	9.5	15	32	10	15	AS7-5553a
M-07-35	G35234	466	468	0.50	0.29	15	7.8	25	16	25	17	AS7-5553a
M-07-35	G35236	468	470	1.77	0.16	21	5.5	90	14	10	28	AS7-5553a
M-07-35	G35237	470	472	6.40	0.23	73	10.5	245	22	10	31	AS7-5553a
M-07-35	G35238	472	474	1.43	0.30	11	5.7	105	20	0.1	24	AS7-5553a
M-07-35	G35240	474	476	1.31	0.30	18	3.9	25	16	0.1	23	AS7-5553a
M-07-35	G35241	476	478	0.58	0.60	33	7.2	10	38	0.1	19	AS7-5553a
M-07-35	G35242	478	480	1.72	0.35	15	3.8	15	10	0.1	18	AS7-5553a
M-07-35	G35243	480	482	0.67	0.35	29	3.5	5	12	0.1	9	AS7-5553a
M-07-35	G35244	482	484	0.39	0.21	25	2.3	10	8	10	10	AS7-5553a
M-07-35	G35245	484	486	0.20	0.06	24	1.1	5	10	0.1	19	AS7-5553a
M-07-35	G35246	486	488	0.85	0.25	39	2.6	10	14	0.1	3	AS7-5553a
M-07-35	G35247	488	490	0.51	0.11	20	1.3	5	6	0.1	3	AS7-5553a
M-07-35	G35248	490	492	0.37	0.16	19	1.4	5	8	0.1	13	AS7-5553a
M-07-35	G35249	492	494	0.25	0.07	39	1	5	10	0.1	3	AS7-5553a
M-07-35	G35250	494	496	0.27	0.20	23	1.7	5	8	0.1	8	AS7-5553a
M-07-35	G35251	496	498	0.88	0.21	20	2.1	30	14	0.1	9	AS7-5588a
M-07-35	G35252	498	500	1.26	0.18	23	2	35	18	0.1	64	AS7-5588a
M-07-35	G35253	500	502	0.79	0.15	63	2	30	22	0.1	52	AS7-5588a
M-07-35	G35254	502	504	0.85	0.16	27	1.9	25	18	10	29	AS7-5588a
M-07-35	G35256	504	506	0.27	0.20	44	2.5	30	22	0.1	14	AS7-5588a
M-07-35	G35257	506	508	0.37	0.26	82	2.4	25	16	0.1	9	AS7-5588a
M-07-35	G35258	508	510	0.31	0.17	24	1.8	25	16	0.1	7	AS7-5588a
M-07-35	G35259	510	512	0.21	0.16	20	2	20	14	5	8	AS7-5588a
M-07-35	G35260	512	514	0.16	0.17	56	1.4	10	14	0.1	9	AS7-5588a
M-07-35	G35261	514	516	0.18	0.12	32	1.1	25	18	5	12	AS7-5588a
M-07-35	G35262	516	518	0.19	0.26	51	1.8	25	18	0.1	12	AS7-5588a
M-07-35	G35263	518	520	0.80	0.22	22	2	30	18	0.1	22	AS7-5588a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-35	G35264	520	522	0.89	0.26	22	2.1	25	18	0.1	30	AS7-5588a
M-07-35	G35265	522	524	0.49	0.29	26	2.7	25	14	5	15	AS7-5588a
M-07-35	G35266	524	526	0.74	0.42	28	3.5	35	22	0.1	30	AS7-5588a
M-07-35	G35267	526	528	0.33	0.28	42	2.1	30	18	0.1	21	AS7-5588a
M-07-35	G35268	528	530	0.64	0.25	67	3.3	40	22	0.1	19	AS7-5588a
M-07-35	G35269	530	532	0.43	0.26	61	2.1	20	22	0.1	21	AS7-5588a
M-07-35	G35270	532	534	0.82	0.17	18	1.9	20	16	0.1	23	AS7-5588a
M-07-35	G35271	534	536	0.47	0.10	32	1.1	20	20	0.1	26	AS7-5588a
M-07-35	G35272	536	538	0.96	0.22	17	1.6	30	16	0.1	25	AS7-5588a
M-07-35	G35273	538	540	0.77	0.19	17	1.9	25	16	0.1	28	AS7-5588a
M-07-35	G35274	540	542	0.65	0.20	18	1.4	25	18	0.1	41	AS7-5588a
M-07-35	G35275	542	544	0.89	0.29	27	2.2	5	16	0.1	23	AS7-5588a
M-07-35	G35276	544	546	0.27	0.39	29	2.9	20	16	0.1	12	AS7-5588a
M-07-35	G35277	546	548	0.81	0.14	20	1.4	15	18	0.1	30	AS7-5588a
M-07-35	G35278	548	550	0.91	0.18	51	1.7	0.1	16	0.1	29	AS7-5588a
M-07-35	G35279	550	552	1.08	0.19	15	2.5	10	18	0.1	58	AS7-5588a
M-07-35	G35280	552	554	0.86	0.27	16	2.4	5	14	0.1	36	AS7-5588a
M-07-35	G35281	554	556	0.70	0.34	17	3.1	25	14	0.1	32	AS7-5588a
M-07-35	G35282	556	558	0.74	0.09	16	0.9	15	16	0.1	34	AS7-5588a
M-07-35	G35283	558	560	1.17	0.32	18	3.2	10	22	0.1	39	AS7-5588a
M-07-35	G35284	560	562	3.00	0.83	12	6.5	20	16	0.1	30	AS7-5588a
M-07-35	G35286	562	564	0.47	0.22	39	2.7	0.1	12	0.1	18	AS7-5593a
M-07-35	G35287	564	566	1.30	0.29	15	3	10	10	0.1	28	AS7-5593a
M-07-35	G35288	566	568	0.65	0.31	18	3.1	5	14	0.1	31	AS7-5593a
M-07-35	G35289	568	570	0.81	0.31	10	3.3	10	12	0.1	55	AS7-5593a
M-07-35	G35290	570	572	0.74	0.55	12	5.2	10	10	0.1	41	AS7-5593a
M-07-35	G35291	572	574.3	0.41	0.17	9	3.1	20	16	0.1	57	AS7-5593a
M-07-35	G35292	574.3	576	0.18	0.06	8	1.1	20	10	0.1	69	AS7-5593a
M-07-35	G35293	576	578	0.50	0.10	12	1.8	30	12	0.1	41	AS7-5593a
M-07-35	G35294	578	580	0.31	0.08	8	1.2	20	10	0.1	41	AS7-5593a
M-07-35	G35295	580	582	0.14	0.06	8	0.7	15	10	0.1	42	AS7-5593a
M-07-35	G35296	582	584	0.08	0.03	8	0.5	10	10	0.1	39	AS7-5593a
M-07-35	G35297	584	586	0.16	0.04	7	0.8	10	10	0.1	33	AS7-5593a
M-07-35	G35298	586	588	0.16	0.05	10	1	25	10	0.1	38	AS7-5593a
M-07-35	G35299	588	590	0.83	0.10	11	1.7	35	14	0.1	30	AS7-5593a
M-07-35	G35300	590	592	0.66	0.07	9	1.1	50	12	0.1	45	AS7-5593a
M-07-35	G35503	592	594	0.54	0.06	9	1	50	12	0.1	52	AS7-5593a
M-07-35	G35504	594	596	0.83	0.15	11	3.5	65	12	0.1	42	AS7-5593a
M-07-35	G35505	596	598	0.58	0.07	11	2.8	35	18	0.1	34	AS7-5593a
M-07-35	G35506	598	600	0.52	0.06	12	1.7	35	14	0.1	76	AS7-5593a
M-07-35	G35507	600	602	0.81	0.13	9	3.1	50	18	0.1	38	AS7-5593a
M-07-35	G35508	602	604	0.34	0.05	11	1.3	15	8	0.1	38	AS7-5593a
M-07-35	G35510	604	606	0.44	0.13	12	2.5	10	18	0.1	62	AS7-5593a
M-07-35	G35511	606	608	1.41	0.26	8	5.6	95	24	0.1	52	AS7-5593a
M-07-35	G35513	608	610	1.50	0.42	8	6.3	70	12	0.1	19	AS7-5593a
M-07-35	G35514	610	612	1.82	0.60	4	8.4	45	10	0.1	13	AS7-5593a
M-07-35	G35515	612	614	1.62	0.59	7	7.8	70	12	0.1	18	AS7-5593a
M-07-35	G35516	614	616	2.43	0.57	5	7.4	25	10	0.1	17	AS7-5593a
M-07-35	G35517	616	618	1.61	0.42	19	5.2	10	12	0.1	24	AS7-5593a
M-07-35	G35518	618	620.24	1.59	0.50	16	5.7	25	14	0.1	30	AS7-5593a
M-07-35	G35520	620.24	622	1.62	0.43	17	4.9	15	10	0.1	24	AS7-5593a
M-07-35	G35521	622	624	1.97	0.49	7	6	15	12	0.1	27	AS7-5593a
M-07-35	G35522	624	626	2.08	0.43	10	5.3	15	12	0.1	29	AS7-5593a
M-07-35	G35523	626	627.4	2.21	0.57	25	6.4	10	10	0.1	19	AS7-5597a
M-07-35	G35524	627.4	629	0.52	0.13	14	2.2	15	28	5	57	AS7-5597a
M-07-35	G35525	629	631	0.58	0.19	17	3.1	0.1	40	0.1	34	AS7-5597a
M-07-35	G35526	631	633	1.21	0.06	15	1.7	10	26	5	37	AS7-5597a
M-07-35	G35527	633	635	0.30	0.06	16	0.9	10	28	0.1	39	AS7-5597a
M-07-35	G35528	635	637	0.46	0.10	23	1.5	20	30	5	54	AS7-5597a
M-07-35	G35529	637	639	0.48	0.12	15	2.2	10	30	0.1	58	AS7-5597a
M-07-35	G35530	639	640.9	0.61	0.17	24	2	15	34	10	107	AS7-5597a
M-07-35	G35531	640.9	643	1.45	0.91	22	9.4	15	22	0.1	47	AS7-5597a
M-07-35	G35532	643	645	1.36	0.46	20	5	10	20	0.1	89	AS7-5597a
M-07-35	G35533	645	647	1.74	0.39	13	5	10	14	0.1	51	AS7-5597a
M-07-35	G35534	647	649	0.67	0.48	19	5.2	5	12	0.1	29	AS7-5597a
M-07-35	G35535	649	651	1.49	0.68	12	6.8	0.1	10	0.1	20	AS7-5597a
M-07-35	G35536	651	653	1.19	0.59	11	5.6	0.1	14	0.1	44	AS7-5597a
M-07-35	G35537	653	655	1.72	0.69	13	5.9	5	8	0.1	21	AS7-5597a
M-07-35	G35538	655	657	1.93	0.63	10	6.2	0.1	10	0.1	23	AS7-5597a
M-07-35	G35539	657	659	1.41	0.30	17	3.7	15	16	0.1	33	AS7-5597a
M-07-35	G35540	659	661	1.68	0.66	14	5.9	0.1	14	0.1	22	AS7-5597a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-35	G35541	661	663	1.56	0.46	17	5.1	0.1	12	0.1	14	AS7-5597a
M-07-35	G35542	663	665	1.22	0.65	16	6	0.1	12	0.1	15	AS7-5597a
M-07-35	G35543	665	667	1.54	0.47	15	5.5	0.1	14	0.1	26	AS7-5597a
M-07-35	G35544	667	669	1.23	0.28	11	3.2	0.1	26	0.1	58	AS7-5597a
M-07-35	G35545	669	671	1.82	0.45	13	4.6	25	18	0.1	26	AS7-5597a
M-07-35	G35546	671	673	1.66	0.33	11	4.5	15	18	0.1	14	AS7-5597a
M-07-35	G35547	673	675	1.36	0.33	23	5	5	26	0.1	40	AS7-5597a
M-07-35	G35548	675	677	1.60	0.45	9	4.8	20	16	0.1	18	AS7-5597a
M-07-35	G35549	677	679	1.33	0.42	10	4.3	10	14	0.1	24	AS7-5597a
M-07-35	G35550	679	681	1.70	0.67	13	7	0.1	12	0.1	23	AS7-5597a
M-07-35	G35552	681	682.14	1.58	0.77	14	8.2	10	10	0.1	11	AS7-5597a
M-07-36	G37110	4.88	6	0.82	0.21	27	3.3	20	36	5	97	AS7-5532a
M-07-36	G37111	6	8	0.74	0.17	34	3.2	45	44	10	113	AS7-5532a
M-07-36	G37112	8	10	0.72	0.17	24	2.9	40	52	5	166	AS7-5532a
M-07-36	G37113	10	12	0.72	0.20	26	3.2	30	46	10	224	AS7-5532a
M-07-36	G37114	12	14	0.97	0.22	33	10.5	35	136	10	501	AS7-5532a
M-07-36	G37115	14	16	0.66	0.18	25	2.7	25	48	10	223	AS7-5532a
M-07-36	G37116	16	18	0.77	0.22	22	2.8	30	40	0.1	236	AS7-5532a
M-07-36	G37117	18	19.1	0.64	0.13	18	2.2	30	38	10	234	AS7-5532a
M-07-36	G37118	19.1	19.75	0.73	0.13	30	7.4	55	44	0.1	54	AS7-5532a
M-07-36	G37119	19.75	21	0.66	0.23	18	3.1	25	34	0.1	89	AS7-5532a
M-07-36	G37120	21	23	0.87	0.24	29	2.3	10	32	0.1	138	AS7-5532a
M-07-36	G37121	23	25	0.53	0.15	23	2.2	20	30	5	120	AS7-5532a
M-07-36	G37123	25	27	0.38	0.11	25	1.5	15	32	0.1	150	AS7-5532a
M-07-36	G37124	27	29	0.26	0.08	26	1.1	15	42	20	185	AS7-5532a
M-07-36	G37126	29	31	0.35	0.11	15	1.5	25	36	5	180	AS7-5532a
M-07-36	G37127	31	33	0.28	0.08	17	1.3	20	46	0.1	209	AS7-5532a
M-07-36	G37128	33	35	0.46	0.11	16	1.6	25	38	0.1	135	AS7-5532a
M-07-36	G37129	35	37	0.41	0.11	16	1.9	30	34	0.1	135	AS7-5532a
M-07-36	G37130	37	39	0.36	0.09	28	1.6	25	56	0.1	179	AS7-5532a
M-07-36	G37131	39	41	0.41	0.11	23	5.7	20	60	0.1	245	AS7-5537a
M-07-36	G37132	41	43	0.29	0.11	26	2	10	38	0.1	138	AS7-5537a
M-07-36	G37133	43	45	0.23	0.10	37	1.5	15	32	0.1	151	AS7-5537a
M-07-36	G37134	45	47	0.34	0.11	26	1.7	10	32	0.1	114	AS7-5537a
M-07-36	G37135	47	48	0.48	0.16	24	2.3	10	26	0.1	102	AS7-5537a
M-07-36	G37136	48	49.35	0.35	0.12	29	2.1	15	32	0.1	117	AS7-5537a
M-07-36	G37137	49.35	51	0.00	0.04	7	0.01	35	50	20	125	AS7-5537a
M-07-36	G37138	51	52.9	0.00	0.01	7	0.01	45	52	25	95	AS7-5537a
M-07-36	G37139	52.9	55	0.30	0.12	44	1.7	20	36	5	154	AS7-5537a
M-07-36	G37141	55	57	0.28	0.09	21	1.3	20	28	15	121	AS7-5537a
M-07-36	G37142	57	59	0.37	0.11	20	2.1	10	34	5	107	AS7-5537a
M-07-36	G37143	59	61	0.41	0.13	20	1.9	0.1	34	0.1	92	AS7-5537a
M-07-36	G37144	61	63	0.28	0.09	14	1.1	15	24	0.1	83	AS7-5537a
M-07-36	G37145	63	65	0.44	0.17	22	2.2	20	26	0.1	97	AS7-5537a
M-07-36	G37146	65	67	0.20	0.08	19	1.2	10	30	0.1	152	AS7-5537a
M-07-36	G37148	67	69	0.28	0.09	20	1.5	20	30	0.1	118	AS7-5537a
M-07-36	G37149	69	71	0.33	0.12	19	1.7	15	30	0.1	115	AS7-5537a
M-07-36	G37150	71	73	0.44	0.15	24	2.1	15	24	10	85	AS7-5537a
M-07-36	G37151	73	75	0.66	0.19	21	2.5	5	24	0.1	67	AS7-5537a
M-07-36	G37152	75	77.11	0.38	0.12	29	1.5	15	24	0.1	84	AS7-5537a
M-07-37	G37153	0.85	2	0.69	0.15	98	1.8	30	78	10	425	AS7-5537a
M-07-37	G37154	2	4	0.82	0.15	103	3.3	40	202	10	601	AS7-5537a
M-07-37	G37155	4	6	0.26	0.06	70	1.2	30	174	10	516	AS7-5537a
M-07-37	G37156	6	8	0.37	0.09	51	1.5	20	106	5	352	AS7-5537a
M-07-37	G37157	8	10	0.39	0.09	117	1.2	40	76	20	306	AS7-5537a
M-07-37	G37158	10	12	0.42	0.08	71	1.3	40	88	15	293	AS7-5537a
M-07-37	G37160	12	14	0.42	0.08	42	1.3	35	78	0.1	305	AS7-5537a
M-07-37	G37161	14	16	0.64	0.13	54	1.9	25	112	15	311	AS7-5537a
M-07-37	G37162	16	18	0.42	0.10	60	1.2	15	98	10	248	AS7-5537a
M-07-37	G37163	18	20	0.64	0.14	90	1.7	25	78	30	339	AS7-5537a
M-07-37	G37164	20	22	0.66	0.11	87	1.6	20	122	15	373	AS7-5537a
M-07-37	G37165	22	24	0.72	0.10	73	1.7	20	124	15	446	AS7-5537a
M-07-37	G37166	24	26	0.58	0.08	65	1.3	35	106	15	419	AS7-5540a
M-07-37	G37167	26	28	0.62	0.10	87	1.6	25	116	5	318	AS7-5540a
M-07-37	G37168	28	30	0.46	0.07	62	0.9	15	114	5	406	AS7-5540a
M-07-37	G37169	30	32	0.40	0.08	92	0.8	45	102	25	415	AS7-5540a
M-07-37	G37171	32	34	1.07	0.12	95	1.7	20	140	0.1	331	AS7-5540a
M-07-37	G37172	34	36	0.77	0.10	66	1.3	20	124	5	475	AS7-5540a
M-07-37	G37173	36	38	0.60	0.12	42	4.4	10	186	0.1	372	AS7-5540a
M-07-37	G37174	38	40	0.57	0.09	49	1.6	35	254	0.1	355	AS7-5540a
M-07-37	G37175	40	42	0.58	0.09	41	1.2	0.1	96	0.1	356	AS7-5540a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-37	G37176	42	44	1.17	0.12	76	2.4	20	174	5	428	AS7-5540a
M-07-37	G37177	44	46	0.97	0.12	124	2.7	0.1	154	0.1	308	AS7-5540a
M-07-37	G37178	46	48	0.86	0.11	58	2.2	25	106	0.1	373	AS7-5540a
M-07-37	G37179	48	50	0.68	0.13	74	2.3	10	44	0.1	319	AS7-5540a
M-07-37	G37180	50	52	0.76	0.10	71	1.7	15	78	10	327	AS7-5540a
M-07-37	G37181	52	54	1.08	0.14	76	2.4	25	84	0.1	518	AS7-5540a
M-07-37	G37182	54	56	0.70	0.11	72	4.2	0.1	184	0.1	1081	AS7-5540a
M-07-37	G37183	56	58	1.36	0.16	82	2.8	20	122	5	252	AS7-5540a
M-07-37	G37185	58	60	0.86	0.09	99	1.4	0.1	66	0.1	391	AS7-5540a
M-07-37	G37186	60	62	0.53	0.07	58	1.4	30	200	0.1	526	AS7-5540a
M-07-37	G37187	62	63.5	1.13	0.13	71	3	0.1	280	0.1	425	AS7-5540a
M-07-37	G37188	63.5	64.9	0.75	0.08	56	2.3	10	264	5	515	AS7-5540a
M-07-37	G37189	64.9	66	0.56	0.08	77	0.9	0.1	78	10	508	AS7-5540a
M-07-37	G37191	66	68	0.90	0.11	84	1.5	10	110	45	849	AS7-5540a
M-07-37	G37192	68	70	0.47	0.09	52	2.9	10	276	0.1	965	AS7-5540a
M-07-37	G37193	70	72	1.30	0.12	66	1.5	0.1	104	25	624	AS7-5540a
M-07-37	G37194	72	74	0.45	0.12	48	2.9	0.1	208	0.1	507	AS7-5540a
M-07-37	G37195	74	76	0.57	0.14	37	4.3	10	194	5	577	AS7-5540a
M-07-37	G37196	76	78	1.20	0.14	51	2	10	76	0.1	479	AS7-5540a
M-07-37	G37197	78	80	1.14	0.16	49	2.2	10	150	0.1	456	AS7-5540a
M-07-37	G37198	80	82	0.63	0.09	62	1.5	15	96	10	398	AS7-5540a
M-07-37	G37199	82	84	0.87	0.16	57	2	25	106	10	328	AS7-5540a
M-07-37	G37200	84	86	0.85	0.15	41	2.5	0.1	148	0.1	335	AS7-5540a
M-07-37	G37201	86	88	0.87	0.12	63	1.9	20	48	0.1	252	AS7-5541a
M-07-37	G37202	88	90	0.68	0.11	53	2.2	25	112	0.1	252	AS7-5541a
M-07-37	G37203	90	92	0.54	0.10	69	1.6	20	62	0.1	211	AS7-5541a
M-07-37	G37204	92	94	0.89	0.15	59	2.4	20	84	0.1	275	AS7-5541a
M-07-37	G37205	94	96	0.67	0.12	36	1.9	25	46	0.1	244	AS7-5541a
M-07-37	G37206	96	98	0.77	0.13	90	1.8	20	70	0.1	164	AS7-5541a
M-07-37	G37207	98	100	0.64	0.11	47	2.3	30	172	5	170	AS7-5541a
M-07-37	G37208	100	102	0.70	0.15	101	1.8	40	106	0.1	300	AS7-5541a
M-07-37	G37210	102	104	0.79	0.12	63	1.5	60	44	0.1	219	AS7-5541a
M-07-37	G37211	104	106	0.39	0.08	49	1.2	30	54	0.1	197	AS7-5541a
M-07-37	G37212	106	108	0.86	0.10	118	1.4	15	64	0.1	285	AS7-5541a
M-07-37	G37213	108	109.5	0.61	0.10	80	1.5	15	48	0.1	239	AS7-5541a
M-07-37	G37214	109.5	110.95	0.46	0.05	39	0.8	15	28	0.1	364	AS7-5541a
M-07-37	G37215	110.95	112.5	0.63	0.12	108	1.5	15	60	0.1	177	AS7-5541a
M-07-37	G37216	112.5	114	0.89	0.15	51	1.8	15	198	0.1	257	AS7-5541a
M-07-37	G37217	114	116	0.56	0.10	45	1.4	10	32	0.1	318	AS7-5541a
M-07-37	G37218	116	118	1.04	0.15	43	2.1	10	30	0.1	219	AS7-5541a
M-07-37	G37219	118	120	0.80	0.14	102	1.8	10	40	0.1	169	AS7-5541a
M-07-37	G37220	120	122	1.04	0.16	118	1.9	10	56	0.1	255	AS7-5541a
M-07-37	G37221	122	124	0.55	0.08	54	1	5	22	0.1	137	AS7-5541a
M-07-37	G37223	124	126	0.57	0.08	51	0.9	5	26	0.1	91	AS7-5541a
M-07-37	G37224	126	128	0.60	0.08	42	0.9	5	22	0.1	184	AS7-5541a
M-07-37	G37225	128	130	0.77	0.09	82	1.2	10	28	0.1	142	AS7-5541a
M-07-37	G37226	130	132	0.58	0.08	40	1.1	20	22	0.1	285	AS7-5541a
M-07-37	G37227	132	134	0.91	0.09	72	1.4	10	30	0.1	337	AS7-5541a
M-07-37	G37228	134	136	1.16	0.13	47	2.2	10	30	0.1	323	AS7-5541a
M-07-37	G37229	136	138	0.84	0.13	66	2.2	10	34	0.1	215	AS7-5541a
M-07-37	G37230	138	140	0.63	0.09	41	1.5	10	32	0.1	212	AS7-5541a
M-07-37	G37231	140	142	0.44	0.06	70	1.2	10	32	0.1	184	AS7-5541a
M-07-37	G37232	142	143.25	0.59	0.09	49	1.4	15	50	0.1	281	AS7-5541a
M-07-37	G37233	143.85	146	1.35	0.14	59	1.8	10	20	0.1	126	AS7-5541a
M-07-37	G37234	146	148	0.99	0.16	48	2.5	20	40	0.1	160	AS7-5541a
M-07-37	G37235	148	150	1.26	0.14	95	2.2	15	24	0.1	177	AS7-5541a
M-07-37	G37236	150	152	0.84	0.09	74	1.1	15	30	10	169	AS7-5542a
M-07-37	G37237	152	154	1.50	0.12	54	2.3	15	36	10	155	AS7-5542a
M-07-37	G37238	154	156	0.84	0.12	94	1.7	10	50	10	193	AS7-5542a
M-07-37	G37239	156	158	0.65	0.07	47	1.1	15	78	15	191	AS7-5542a
M-07-37	G37240	158	160	0.86	0.13	43	1.8	20	42	15	210	AS7-5542a
M-07-37	G37241	160	162	0.80	0.11	80	1.3	20	50	15	147	AS7-5542a
M-07-37	G37243	162	164	0.90	0.14	54	1.6	10	58	10	118	AS7-5542a
M-07-37	G37244	164	166	1.29	0.17	107	1.8	15	28	0.1	132	AS7-5542a
M-07-37	G37245	166	168	0.76	0.14	56	1.8	15	36	0.1	77	AS7-5542a
M-07-37	G37246	168	170	0.62	0.14	65	2	10	68	0.1	85	AS7-5542a
M-07-37	G37248	170	172	1.08	0.15	79	1.3	15	46	5	149	AS7-5542a
M-07-37	G37249	172	174	0.96	0.14	114	1.8	30	48	10	270	AS7-5542a
M-07-37	G37250	174	176	0.72	0.12	41	1.4	30	36	15	270	AS7-5542a
M-07-37	G37251	176	178	0.96	0.12	156	2.3	15	74	0.1	97	AS7-5542a
M-07-37	G37252	178	180	1.28	0.19	69	2.5	20	48	10	257	AS7-5542a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-37	G37253	180	182	1.00	0.16	54	1.5	20	56	15	231	AS7-5542a
M-07-37	G37254	182	184	1.02	0.13	57	2.3	20	200	5	317	AS7-5542a
M-07-37	G37255	184	186	1.11	0.17	51	2	20	46	15	206	AS7-5542a
M-07-37	G37256	186	188	0.81	0.12	67	1.5	15	40	5	257	AS7-5542a
M-07-37	G37257	188	190	0.84	0.13	61	1.5	5	56	0.1	161	AS7-5542a
M-07-37	G37258	190	191.6	1.21	0.15	137	1.6	10	70	5	157	AS7-5542a
M-07-37	G37259	191.6	193	1.34	0.19	116	2.1	15	34	0.1	122	AS7-5542a
M-07-37	G37260	193	195	0.81	0.16	54	2.3	25	64	0.1	104	AS7-5542a
M-07-37	G37262	195	197	1.16	0.16	99	2	20	30	10	117	AS7-5542a
M-07-37	G37263	197	199	0.98	0.14	58	2.5	20	38	0.1	121	AS7-5542a
M-07-37	G37264	199	201	1.03	0.18	89	2.8	10	30	5	149	AS7-5542a
M-07-37	G37265	201	203	0.98	0.18	71	2.8	10	44	0.1	163	AS7-5542a
M-07-37	G37266	203	204.25	0.96	0.13	65	2.2	10	52	0.1	220	AS7-5542a
M-07-37	G37267	204.25	205.44	0.90	0.14	77	1.7	30	54	10	326	AS7-5542a
M-07-37	G37268	205.44	207	0.86	0.20	94	1.8	20	58	0.1	127	AS7-5542a
M-07-37	G37269	207	209	0.76	0.14	128	1.7	5	40	0.1	66	AS7-5542a
M-07-37	G37270	209	211	1.09	0.16	118	1.9	25	38	0.1	92	AS7-5542a
M-07-37	G37271	211	213	0.54	0.10	172	1.6	65	194	5	123	AS7-5543a
M-07-37	G37272	213	215	0.85	0.15	169	1.6	70	24	0.1	215	AS7-5543a
M-07-37	G37273	215	217	0.46	0.12	210	2.2	170	32	30	74	AS7-5543a
M-07-37	G37274	217	219	0.54	0.11	137	2	75	42	15	43	AS7-5543a
M-07-37	G37275	219	221	0.94	0.12	65	1.6	20	20	0.1	69	AS7-5543a
M-07-37	G37276	221	223	1.11	0.14	180	1.8	45	40	0.1	196	AS7-5543a
M-07-37	G37277	223	225	0.90	0.18	132	2.4	30	30	0.1	655	AS7-5543a
M-07-37	G37278	225	227	1.88	0.14	109	5.7	300	168	25	2081	AS7-5543a
M-07-37	G37279	227	229	0.71	0.15	193	2.5	135	40	15	65	AS7-5543a
M-07-37	G37281	229	231	0.49	0.17	125	2.6	240	28	25	74	AS7-5543a
M-07-37	G37282	231	233	0.72	0.14	111	1.9	115	30	10	46	AS7-5543a
M-07-37	G37283	233	235	0.70	0.13	139	2.2	120	34	15	63	AS7-5543a
M-07-37	G37284	235	237	0.70	0.18	75	3	175	30	25	90	AS7-5543a
M-07-37	G37285	237	239	0.76	0.12	176	1.7	65	40	5	122	AS7-5543a
M-07-37	G37286	239	241	1.24	0.16	107	1.3	75	40	0.1	87	AS7-5543a
M-07-37	G37287	241	243	0.49	0.10	141	0.9	165	22	15	69	AS7-5543a
M-07-37	G37288	243	245	0.38	0.10	99	1.1	385	14	35	83	AS7-5543a
M-07-37	G37289	245	247	0.40	0.14	89	0.9	275	32	25	73	AS7-5543a
M-07-37	G37291	247	249	0.47	0.15	75	0.5	45	24	0.1	29	AS7-5543a
M-07-37	G37292	249	251	0.86	0.15	128	1	310	44	40	92	AS7-5543a
M-07-37	G37293	251	253	1.22	0.16	223	1.7	230	42	35	99	AS7-5543a
M-07-37	G37294	253	255	0.86	0.17	100	1.5	55	44	15	64	AS7-5543a
M-07-37	G37296	255	257	0.86	0.15	130	1.2	65	60	10	55	AS7-5543a
M-07-37	G37297	257	259	0.39	0.12	137	0.7	15	42	0.1	32	AS7-5543a
M-07-37	G37298	259	261	0.37	0.06	183	1.3	120	16	25	41	AS7-5543a
M-07-37	G37299	261	263	0.58	0.15	162	0.9	15	24	0.1	17	AS7-5543a
M-07-37	G37300	263	265	0.50	0.13	99	1.3	10	66	0.1	39	AS7-5543a
M-07-37	G37301	265	267	0.54	0.12	215	1.1	10	38	0.1	29	AS7-5543a
M-07-37	G37302	267	269	0.68	0.14	153	1	10	32	0.1	28	AS7-5543a
M-07-37	G37303	269	271	0.77	0.12	280	1.2	15	52	0.1	31	AS7-5543a
M-07-37	G37304	271	273	1.06	0.14	246	1.4	45	74	0.1	44	AS7-5543a
M-07-37	G37305	273	275	0.77	0.12	308	1.7	55	48	15	58	AS7-5543a
M-07-37	G37306	275	277	0.70	0.10	223	1	10	84	0.1	38	AS7-5547a
M-07-37	G37307	277	278.89	0.74	0.12	122	1.4	10	86	0.1	33	AS7-5547a
M-07-37	G37308	278.89	281	0.62	0.09	131	1.1	10	68	0.1	45	AS7-5547a
M-07-37	G37309	281	283	0.73	0.10	296	1.1	5	56	0.1	49	AS7-5547a
M-07-37	G37310	283	285	0.59	0.07	300	0.7	25	94	0.1	65	AS7-5547a
M-07-37	G37311	285	287	1.19	0.11	195	1.1	25	52	0.1	58	AS7-5547a
M-07-37	G37312	287	289	0.91	0.13	192	2	150	56	100	115	AS7-5547a
M-07-37	G37313	289	291	0.80	0.12	118	1.4	75	84	35	77	AS7-5547a
M-07-37	G37314	291	293	0.82	0.12	411	0.9	20	58	0.1	46	AS7-5547a
M-07-37	G37315	293	295	0.62	0.14	81	1.6	70	82	20	60	AS7-5547a
M-07-37	G37316	295	297	0.59	0.09	154	0.6	30	26	0.1	96	AS7-5547a
M-07-37	G37317	297	299	1.39	0.11	135	0.7	25	24	0.1	29	AS7-5547a
M-07-37	G37318	299	301	0.79	0.11	189	1.1	30	24	0.1	27	AS7-5547a
M-07-37	G37320	301	303	0.65	0.09	91	1.1	15	30	0.1	43	AS7-5547a
M-07-37	G37321	303	305	0.81	0.10	122	1.2	30	48	0.1	53	AS7-5547a
M-07-37	G37322	305	307	0.55	0.10	175	1.2	30	46	0.1	100	AS7-5547a
M-07-37	G37323	307	309	0.60	0.15	165	0.9	45	40	0.1	92	AS7-5547a
M-07-37	G37324	309	310.35	0.23	0.09	518	0.5	15	32	0.1	67	AS7-5547a
M-07-37	G37325	310.35	311.7	0.24	0.05	100	1.2	110	66	15	57	AS7-5547a
M-07-37	G37326	311.7	313	0.25	0.09	164	0.7	30	54	0.1	93	AS7-5547a
M-07-37	G37327	313	315	0.86	0.12	151	0.8	10	58	0.1	139	AS7-5547a
M-07-37	G37328	315	317	0.59	0.06	106	0.7	5	102	0.1	89	AS7-5547a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-37	G37330	317	319	0.79	0.11	159	1.2	10	44	0.1	58	AS7-5547a
M-07-37	G37331	319	321	0.86	0.09	147	1.3	15	32	0.1	57	AS7-5547a
M-07-37	G37332	321	323	0.82	0.10	225	1.5	30	52	0.1	46	AS7-5547a
M-07-37	G37333	323	325	0.65	0.06	101	0.8	20	24	0.1	55	AS7-5547a
M-07-37	G37335	325	327	0.83	0.06	230	1	30	34	10	156	AS7-5547a
M-07-37	G37336	327	329	0.78	0.05	60	1.1	15	30	0.1	119	AS7-5547a
M-07-37	G37337	329	331	0.67	0.08	167	1.3	10	64	0.1	96	AS7-5547a
M-07-37	G37338	331	333	0.65	0.07	95	0.9	10	68	0.1	108	AS7-5547a
M-07-37	G37339	333	335	0.36	0.05	62	1.1	15	80	0.1	104	AS7-5547a
M-07-37	G37340	335	337	0.95	0.06	223	0.9	5	54	0.1	72	AS7-5547a
M-07-37	G37341	337	339	0.38	0.07	192	0.8	0.1	46	0.1	37	AS7-5548a
M-07-37	G37342	339	340.3	0.36	0.05	291	0.6	0.1	44	0.1	62	AS7-5548a
M-07-37	G37343	340.3	342	0.50	0.05	95	0.6	0.1	26	0.1	84	AS7-5548a
M-07-37	G37344	342	344	0.43	0.05	69	0.6	0.1	48	0.1	76	AS7-5548a
M-07-37	G37345	344	346	0.34	0.04	107	0.6	0.1	84	10	66	AS7-5548a
M-07-37	G37346	346	348	0.42	0.04	60	0.5	0.1	58	10	69	AS7-5548a
M-07-37	G37347	348	350	0.29	0.04	44	0.4	0.1	42	10	80	AS7-5548a
M-07-37	G37348	350	352	0.47	0.05	24	0.6	0.1	58	10	55	AS7-5548a
M-07-37	G37349	352	354	0.30	0.03	102	0.6	0.1	88	10	43	AS7-5548a
M-07-37	G37350	354	356	0.24	0.02	65	0.5	0.1	88	10	43	AS7-5548a
M-07-37	G37351	356	358	0.35	0.04	52	0.4	0.1	42	20	61	AS7-5548a
M-07-37	G37352	358	360	0.30	0.03	16	0.3	0.1	34	0.1	37	AS7-5548a
M-07-37	G37353	360	362	0.57	0.07	32	0.6	0.1	46	10	56	AS7-5548a
M-07-37	G37354	362	364	0.50	0.05	67	0.6	0.1	58	0.1	63	AS7-5548a
M-07-37	G37355	364	366	0.38	0.04	26	0.7	0.1	78	10	35	AS7-5548a
M-07-37	G37357	366	368	0.31	0.03	84	0.3	0.1	36	10	52	AS7-5548a
M-07-37	G37358	368	370	0.18	0.02	27	0.4	0.1	38	0.1	47	AS7-5548a
M-07-37	G37359	370	372	0.23	0.03	45	0.4	0.1	38	5	43	AS7-5548a
M-07-37	G37360	372	374	0.23	0.02	42	0.4	0.1	42	0.1	61	AS7-5548a
M-07-37	G37361	374	376	0.36	0.03	51	0.7	0.1	86	0.1	58	AS7-5548a
M-07-37	G37362	376	378	0.33	0.02	81	0.4	0.1	38	10	67	AS7-5548a
M-07-37	G37363	378	380	0.26	0.02	27	0.3	0.1	26	10	89	AS7-5548a
M-07-37	G37364	380	382	0.36	0.03	36	0.4	0.1	28	15	85	AS7-5548a
M-07-37	G37365	382	384	0.30	0.03	12	0.3	0.1	22	0.1	65	AS7-5548a
M-07-37	G37366	384	386	0.31	0.02	14	0.4	0.1	22	0.1	55	AS7-5548a
M-07-37	G37367	386	388	0.21	0.01	23	0.3	0.1	22	0.1	83	AS7-5548a
M-07-37	G37368	388	390	0.22	0.02	18	0.3	0.1	22	15	62	AS7-5548a
M-07-37	G37370	390	392	0.16	0.01	10	0.2	0.1	20	0.1	51	AS7-5548a
M-07-37	G37371	392	394	0.18	0.01	10	0.3	0.1	28	0.1	29	AS7-5548a
M-07-37	G37372	394	396	0.20	0.01	29	0.2	0.1	30	5	79	AS7-5548a
M-07-37	G37373	396	398	0.31	0.03	26	0.3	0.1	20	35	112	AS7-5548a
M-07-37	G37374	398	400	0.36	0.02	57	0.2	0.1	26	0.1	121	AS7-5548a
M-07-37	G37375	400	402	0.19	0.01	24	0.3	0.1	32	0.1	52	AS7-5548a
M-07-37	G37376	402	404	0.42	0.03	8	0.3	0.1	20	0.1	49	AS7-5554a
M-07-37	G37377	404	406	0.55	0.02	13	0.2	0.1	18	0.1	37	AS7-5554a
M-07-37	G37378	406	408	0.44	0.03	11	0.3	0.1	46	0.1	47	AS7-5554a
M-07-37	G37379	408	410	0.18	0.01	6	0.2	0.1	30	0.1	16	AS7-5554a
M-07-37	G37380	410	412	0.28	0.02	5	0.4	0.1	90	0.1	63	AS7-5554a
M-07-37	G37381	412	414	0.42	0.01	8	0.2	0.1	42	0.1	33	AS7-5554a
M-07-37	G37383	414	416	0.19	0.02	9	0.3	10	28	0.1	21	AS7-5554a
M-07-37	G37384	416	417.8	0.16	0.01	7	0.2	15	38	0.1	14	AS7-5554a
M-07-37	G37385	417.8	419	0.14	0.01	9	0.3	15	20	0.1	14	AS7-5554a
M-07-37	G37386	419	421	0.07	0.00	6	0.01	0.1	8	0.1	0.01	AS7-5554a
M-07-37	G37387	421	423	0.08	0.01	7	0.01	5	20	0.1	9	AS7-5554a
M-07-37	G37388	423	425	0.09	0.00	9	0.01	0.1	28	0.1	7	AS7-5554a
M-07-37	G37389	425	427	0.16	0.01	16	0.2	15	38	0.1	16	AS7-5554a
M-07-37	G37390	427	428.24	0.38	0.02	7	0.4	50	38	0.1	35	AS7-5554a
M-07-38	E192401	13.45	15	0.26	0.12	18	0.9	15	30	0.1	75	AS7-5555a
M-07-38	E192402	15	17	0.18	0.09	31	0.9	5	24	0.1	67	AS7-5555a
M-07-38	E192403	17	19	0.14	0.08	23	1	0.1	28	0.1	69	AS7-5555a
M-07-38	E192404	19	21	0.11	0.07	17	0.8	0.1	28	0.1	71	AS7-5555a
M-07-38	E192405	21	23	0.18	0.06	27	0.8	0.1	22	0.1	60	AS7-5555a
M-07-38	E192406	23	25	0.18	0.07	22	1	0.1	24	0.1	58	AS7-5555a
M-07-38	E192407	25	27	0.19	0.07	48	0.9	0.1	24	0.1	59	AS7-5555a
M-07-38	E192409	27	29	0.38	0.10	31	1.3	0.1	24	0.1	66	AS7-5555a
M-07-38	E192410	29	31	0.11	0.05	39	0.7	0.1	22	0.1	59	AS7-5555a
M-07-38	E192411	31	33	0.24	0.08	42	1	0.1	22	0.1	56	AS7-5555a
M-07-38	E192412	33	35	0.18	0.07	31	1.1	0.1	20	0.1	47	AS7-5555a
M-07-38	E192413	35	37	0.21	0.07	34	0.9	0.1	22	0.1	63	AS7-5555a
M-07-38	E192414	37	39	0.26	0.08	36	1.3	0.1	24	0.1	53	AS7-5555a
M-07-38	E192416	39	41	0.14	0.08	54	1.3	0.1	20	0.1	49	AS7-5555a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-38	E192417	41	43	0.23	0.08	46	1.2	5	40	0.1	66	AS7-5555a
M-07-38	E192418	43	45	0.22	0.07	39	1.6	0.1	22	0.1	55	AS7-5555a
M-07-38	E192419	45	47	0.35	0.20	36	52.9	20	1456	15	2133	AS7-5555a
M-07-38	E192420	47	49	0.48	0.29	48	23.4	30	984	15	3100	AS7-5555a
M-07-38	E192421	49	50.29	0.18	0.06	44	1.1	15	42	10	89	AS7-5555a
M-07-38	E192422	52.1	54	0.32	0.13	44	3.3	10	36	10	91	AS7-5555a
M-07-38	E192423	54	56	0.31	0.14	35	6.3	35	366	20	533	AS7-5555a
M-07-38	E192424	56	58	0.29	0.11	45	1.7	20	34	0.1	91	AS7-5555a
M-07-38	E192425	58	60	0.25	0.09	72	1	15	32	5	69	AS7-5555a
M-07-38	E192426	60	62	0.30	0.13	45	1.8	30	30	15	89	AS7-5555a
M-07-38	E192427	62	64	0.21	0.09	25	1.1	30	32	0.1	78	AS7-5555a
M-07-38	E192428	64	66	0.69	0.21	96	2.4	30	60	0.1	91	AS7-5555a
M-07-38	E192429	66	68	0.44	0.13	60	1.3	0.1	18	25	52	AS7-5555a
M-07-38	E192430	68	70	0.24	0.10	33	0.9	0.1	22	10	61	AS7-5555a
M-07-38	E192431	70	72	0.23	0.09	68	0.9	0.1	24	10	56	AS7-5555a
M-07-38	E192433	72	74	0.18	0.08	35	0.7	0.1	22	5	57	AS7-5555a
M-07-38	E192434	74	76	0.21	0.09	31	0.9	0.1	24	10	59	AS7-5555a
M-07-38	E192435	76	78	0.24	0.09	45	0.8	0.1	24	10	53	AS7-5555a
M-07-38	E192436	78	80	0.41	0.12	60	1.1	0.1	22	10	54	AS7-5560a
M-07-38	E192437	80	82	0.25	0.08	73	0.8	0.1	26	0.1	55	AS7-5560a
M-07-38	E192438	82	84	0.39	0.08	32	0.8	0.1	16	5	33	AS7-5560a
M-07-38	E192439	84	86	0.23	0.05	24	0.5	5	16	0.1	26	AS7-5560a
M-07-38	E192440	86	88	0.34	0.11	32	0.8	15	26	10	57	AS7-5560a
M-07-38	E192442	88	90	0.32	0.10	46	0.9	5	24	10	54	AS7-5560a
M-07-38	E192443	90	92	0.30	0.09	35	0.8	10	22	5	52	AS7-5560a
M-07-38	E192444	92	94	0.35	0.12	42	1.2	10	28	5	61	AS7-5560a
M-07-38	E192445	94	96	0.32	0.09	44	0.9	10	28	10	66	AS7-5560a
M-07-38	E192446	96	98	0.30	0.12	32	1	10	28	20	64	AS7-5560a
M-07-38	E192447	98	100	0.44	0.16	37	1.3	0.1	30	5	62	AS7-5560a
M-07-38	E192448	100	102	0.37	0.11	32	0.9	10	30	10	66	AS7-5560a
M-07-38	E192449	102	104	0.43	0.16	54	1.4	10	32	10	58	AS7-5560a
M-07-38	E192450	104	106	0.50	0.20	51	1.7	10	28	10	51	AS7-5560a
M-07-38	E192451	106	108	0.32	0.12	48	1.3	10	30	10	69	AS7-5560a
M-07-38	E192452	108	110	0.38	0.12	47	1.1	10	34	10	65	AS7-5560a
M-07-38	E192453	110	112	0.33	0.11	37	1	5	28	5	76	AS7-5560a
M-07-38	E192454	112	114	0.32	0.10	115	0.8	5	24	0.1	61	AS7-5560a
M-07-38	E192455	114	116	0.30	0.11	123	0.9	5	28	10	66	AS7-5560a
M-07-38	E192456	116	118	0.29	0.12	56	1.2	5	26	5	70	AS7-5560a
M-07-38	E192457	118	120	0.20	0.08	90	0.7	10	28	20	88	AS7-5560a
M-07-38	E192458	120	122	0.16	0.06	82	0.6	5	26	5	71	AS7-5560a
M-07-38	E192459	122	124	0.21	0.09	133	1.4	15	202	5	201	AS7-5560a
M-07-38	E192461	124	126	0.29	0.11	51	1.6	10	132	10	320	AS7-5560a
M-07-38	E192462	126	128	0.25	0.10	62	1.4	15	52	5	111	AS7-5560a
M-07-38	E192463	128	130	0.29	0.09	73	1.7	10	32	5	68	AS7-5560a
M-07-38	E192464	130	132	0.21	0.08	58	1.6	5	60	10	79	AS7-5560a
M-07-38	E192465	132	134	0.12	0.06	24	1	15	102	10	112	AS7-5560a
M-07-38	E192466	134	136	1.09	0.12	7	3.6	30	578	20	617	AS7-5560a
M-07-38	E192467	136	138	0.00	0.01	5	0.01	30	66	20	73	AS7-5560a
M-07-38	E192468	138	140	0.24	0.12	32	3.8	25	34	15	87	AS7-5560a
M-07-38	E192469	140	142	0.39	0.12	32	3.9	15	40	10	83	AS7-5560a
M-07-38	E192470	142	144	0.54	0.14	36	2.6	10	68	10	67	AS7-5560a
M-07-38	E192471	144	146	0.37	0.14	51		20	42	0.1	70	AS7-5562a
M-07-38	E192472	146	148	0.14	0.05	25		30	44	0.1	86	AS7-5562a
M-07-38	E192473	148	150	0.21	0.08	29		25	36	0.1	80	AS7-5562a
M-07-38	E192474	150	152	0.25	0.10	44		20	32	10	73	AS7-5562a
M-07-38	E192475	152	154	0.28	0.10	42		25	32	10	70	AS7-5562a
M-07-38	E192476	154	156	0.29	0.12	76		20	42	0.1	65	AS7-5562a
M-07-38	E192477	156	158	0.21	0.07	38		25	30	0.1	52	AS7-5562a
M-07-38	E192478	158	160	0.40	0.11	45		15	36	0.1	60	AS7-5562a
M-07-38	E192479	160	162	0.38	0.12	44		30	46	10	74	AS7-5562a
M-07-38	E192480	162	164	0.59	0.21	54		20	34	10	62	AS7-5562a
M-07-38	E192482	164	166	0.76	0.27	48		25	40	10	72	AS7-5562a
M-07-38	E192483	166	168	0.44	0.19	36		40	42	0.1	69	AS7-5562a
M-07-38	E192484	168	170	0.39	0.15	40		25	32	0.1	64	AS7-5562a
M-07-38	E192485	170	172	0.43	0.11	30		25	54	10	297	AS7-5562a
M-07-38	E192486	172	174	0.49	0.13	46		25	78	5	69	AS7-5562a
M-07-38	E192487	174	176	1.09	0.13	31		30	106	0.1	75	AS7-5562a
M-07-38	E192488	176	178	0.75	0.21	38		30	40	10	76	AS7-5562a
M-07-38	E192489	178	180	0.47	0.17	33		40	36	10	91	AS7-5562a
M-07-38	E192490	180	182	0.34	0.12	38		20	34	0.1	94	AS7-5562a
M-07-38	E192491	182	184	0.36	0.12	46		15	32	5	92	AS7-5562a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-38	E192493	184	186	0.58	0.19	46		25	38	0.1	123	AS7-5562a
M-07-38	E192494	186	188	0.36	0.13	39		10	40	0.1	83	AS7-5562a
M-07-38	E192495	188	190	0.29	0.10	49		30	30	5	83	AS7-5562a
M-07-38	E192497	190	192	0.40	0.14	49		40	44	5	119	AS7-5562a
M-07-38	E192498	192	194	0.61	0.19	46		40	40	0.1	84	AS7-5562a
M-07-38	E192499	194	196	0.46	0.10	60		40	40	10	61	AS7-5562a
M-07-38	E192500	196	198	0.30	0.11	41		45	36	0.1	83	AS7-5562a
M-07-38	E192501	198	199.7	0.26	0.10	35		30	30	0.1	88	AS7-5562a
M-07-38	E192502	199.7	201.35	0.17	0.07	43		30	22	10	57	AS7-5562a
M-07-38	E192503	201.35	203	0.33	0.19	37		25	134	0.1	75	AS7-5562a
M-07-38	E192504	203	205	0.40	0.14	33		25	66	0.1	120	AS7-5562a
M-07-38	E192505	205	207	0.58	0.23	23		25	52	0.1	121	AS7-5562a
M-07-38	E192506	207	209	0.35	0.15	36		10	30	10	100	AS7-5561a
M-07-38	E192507	209	211	0.50	0.21	19		10	24	0.1	73	AS7-5561a
M-07-38	E192508	211	213	0.20	0.08	17		10	134	10	73	AS7-5561a
M-07-38	E192509	213	215	0.37	0.16	47		15	24	0.1	69	AS7-5561a
M-07-38	E192510	215	217	0.48	0.16	49		5	42	0.1	102	AS7-5561a
M-07-38	E192511	217	219	0.42	0.15	102		15	36	10	94	AS7-5561a
M-07-38	E192512	219	221	0.42	0.19	75		15	38	0.1	106	AS7-5561a
M-07-38	E192513	221	223	0.22	0.11	42		15	30	15	86	AS7-5561a
M-07-38	E192514	223	225	0.33	0.17	129		20	24	5	88	AS7-5561a
M-07-38	E192515	225	227	0.23	0.13	43		10	28	10	104	AS7-5561a
M-07-38	E192516	227	229	0.70	0.10	50		15	34	0.1	98	AS7-5561a
M-07-38	E192517	229	231	0.27	0.12	79		10	32	10	108	AS7-5561a
M-07-38	E192518	231	233	0.52	0.21	94		20	32	5	90	AS7-5561a
M-07-38	E192519	233	235	0.75	0.36	154		20	28	5	98	AS7-5561a
M-07-38	E192520	235	237	0.30	0.11	73		10	32	5	106	AS7-5561a
M-07-38	E192521	237	239	0.45	0.17	107		10	28	0.1	117	AS7-5561a
M-07-38	E192522	239	241	0.43	0.14	103		5	24	0.1	89	AS7-5561a
M-07-38	E192523	241	243	0.33	0.11	80		15	24	0.1	80	AS7-5561a
M-07-38	E192524	243	244.2	0.45	0.19	77		15	36	5	93	AS7-5561a
M-07-38	E192525	244.2	245.35	0.30	0.18	71		20	110	0.1	207	AS7-5561a
M-07-38	E192526	245.35	247	0.37	0.15	59		35	78	10	200	AS7-5561a
M-07-38	E192527	247	249	0.32	0.10	75		30	32	10	78	AS7-5561a
M-07-38	E192529	249	251	0.38	0.12	64		45	54	10	121	AS7-5561a
M-07-38	E192530	251	253	0.29	0.12	74		30	62	0.1	108	AS7-5561a
M-07-38	E192531	253	255	0.37	0.14	65		25	36	10	117	AS7-5561a
M-07-38	E192532	255	257	0.15	0.05	39		15	22	0.1	44	AS7-5561a
M-07-38	E192534	257	259	0.17	0.08	35		20	28	10	50	AS7-5561a
M-07-38	E192535	259	261	0.16	0.08	36		25	22	10	57	AS7-5561a
M-07-38	E192536	261	263	0.25	0.13	235		30	48	5	68	AS7-5561a
M-07-38	E192537	263	265	0.20	0.09	48		20	36	0.1	59	AS7-5561a
M-07-38	E192538	265	267	0.48	0.20	50		25	32	5	57	AS7-5561a
M-07-38	E192539	267	269	0.49	0.22	172		25	28	5	68	AS7-5561a
M-07-38	E192540	269	271	0.34	0.13	271		30	38	5	47	AS7-5561a
M-07-38	E192541	271	273	0.44	0.17	292	1.4	10	28	0.1	47	AS7-5565a
M-07-38	E192542	273	275	0.26	0.20	79	10.4	0.1	140	5	133	AS7-5565a
M-07-38	E192543	275	277	0.22	0.10	37	1.5	0.1	38	5	70	AS7-5565a
M-07-38	E192544	277	279	0.16	0.07	77	1.6	0.1	82	10	348	AS7-5565a
M-07-38	E192545	279	281	0.16	0.08	35	0.7	0.1	26	5	63	AS7-5565a
M-07-38	E192546	281	283	0.23	0.08	30	0.7	0.1	28	15	63	AS7-5565a
M-07-38	E192547	283	285	0.27	0.12	31	0.9	0.1	34	0.1	60	AS7-5565a
M-07-38	E192548	285	287	0.46	0.15	38	1.2	0.1	28	10	50	AS7-5565a
M-07-38	E192549	287	289	0.45	0.21	51	1.6	5	30	0.1	46	AS7-5565a
M-07-38	E192550	289	291	0.30	0.10	29	0.9	0.1	24	10	55	AS7-5565a
M-07-38	E192551	291	293	0.22	0.09	45	0.7	0.1	22	0.1	59	AS7-5565a
M-07-38	E192552	293	295	0.27	0.11	193	0.9	0.1	34	10	95	AS7-5565a
M-07-38	E192554	295	297	0.36	0.08	184	0.8	5	30	10	84	AS7-5565a
M-07-38	E192555	297	298.5	0.50	0.14	65	1.4	0.1	36	5	104	AS7-5565a
M-07-38	E192556	298.5	300.21	0.21	0.10	66	1.1	0.1	26	0.1	63	AS7-5565a
M-07-39	G37391	6.96	9	0.22	0.08	44	0.5	0.1	14	0.1	46	AS7-5554a
M-07-39	G37392	9	11	0.23	0.09	40	1.1	0.1	16	0.1	47	AS7-5554a
M-07-39	G37393	11.58	12.3	0.31	0.08	56	0.9	0.1	20	0.1	60	AS7-5554a
M-07-39	G37394	13.9	16	0.22	0.07	31	0.8	20	36	0.1	104	AS7-5554a
M-07-39	G37395	16	18	0.23	0.10	31	0.9	5	28	0.1	75	AS7-5554a
M-07-39	G37396	18	19.4	0.50	0.10	43	0.9	10	30	5	73	AS7-5554a
M-07-39	G37397	20.65	22	0.26	0.10	47	1	0.1	32	10	57	AS7-5554a
M-07-39	G37398	22	24	0.31	0.10	29	1	15	32	0.1	73	AS7-5554a
M-07-39	G37399	24	26	0.28	0.12	42	1.1	0.1	28	0.1	66	AS7-5554a
M-07-39	G37400	26	27.5	0.77	0.15	26	4.4	5	68	5	99	AS7-5554a
M-07-39	G37401	27.5	29	0.78	0.15	35	8.4	15	490	0.1	694	AS7-5554a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-39	G37402	29	31	0.34	0.13	30	2.9	0.1	124	0.1	377	AS7-5554a
M-07-39	G37403	31	33	0.30	0.12	33	1.1	5	34	0.1	82	AS7-5554a
M-07-39	G37405	33	35	0.45	0.17	28	1.4	0.1	30	0.1	66	AS7-5554a
M-07-39	G37406	35	37	0.84	0.21	40	1.9	0.1	32	0.1	55	AS7-5554a
M-07-39	G37407	37	39	0.26	0.12	20	0.7	0.1	38	0.1	61	AS7-5554a
M-07-39	G37408	39	41	0.00	0.01	7	0.01	40	58	20	69	AS7-5554a
M-07-39	G37409	41	43	0.51	0.14	33	1.5	0.1	44	5	71	AS7-5554a
M-07-39	G37410	43	45	0.57	0.18	24	1.5	0.1	26	0.1	56	AS7-5554a
M-07-39	G37411	45	47	0.50	0.14	31	1.6	20	34	10	70	AS7-5563a
M-07-39	G37412	47	49	0.71	0.20	34	3.2	20	34	10	90	AS7-5563a
M-07-39	G37413	49	51	0.93	0.30	56	3.6	25	40	0.1	206	AS7-5563a
M-07-39	G37414	51	53	0.84	0.24	53	2.8	20	32	10	213	AS7-5563a
M-07-39	G37416	53	55	0.66	0.14	180	2	45	40	0.1	196	AS7-5563a
M-07-39	G37417	55	57	0.74	0.20	47	2.3	30	46	10	175	AS7-5563a
M-07-39	G37418	57	59	0.87	0.14	109	2.8	300	168	25	2081	AS7-5563a
M-07-39	G37419	59	61	0.66	0.15	51	1.7	20	36	5	228	AS7-5563a
M-07-39	G37420	61	63	0.49	0.13	34	1.6	20	48	0.1	214	AS7-5563a
M-07-39	G37421	63	65	0.88	0.22	117	2.8	25	42	0.1	155	AS7-5563a
M-07-39	G37422	65	67	0.49	0.14	57	1.9	35	60	10	210	AS7-5563a
M-07-39	G37423	67	69	0.54	0.13	39	1.7	30	44	0.1	180	AS7-5563a
M-07-39	G37424	69	71	0.70	0.17	42	2.4	45	50	0.1	97	AS7-5563a
M-07-39	G37425	71	73	0.81	0.25	27	4.7	35	42	0.1	122	AS7-5563a
M-07-39	G37426	73	75	0.73	0.16	107	3.7	75	40	0.1	87	AS7-5563a
M-07-39	G37428	75	77	0.54	0.14	31	1.6	25	40	0.1	169	AS7-5563a
M-07-39	G37429	77	79	1.21	0.30	39	3.7	30	40	5	89	AS7-5563a
M-07-39	G37430	79	81	0.83	0.27	66	3.1	40	40	0.1	158	AS7-5563a
M-07-39	G37431	81	83	0.66	0.17	56	2.3	25	34	0.1	179	AS7-5563a
M-07-39	G37433	83	85	0.55	0.16	223	1.9	230	42	35	99	AS7-5563a
M-07-39	G37434	85	87	0.55	0.14	78	2	20	42	0.1	190	AS7-5563a
M-07-39	G37435	87	89	0.56	0.16	50	2	30	38	0.1	165	AS7-5563a
M-07-39	G37436	89	91	0.67	0.18	69	2.1	30	38	15	137	AS7-5563a
M-07-39	G37437	91	93	0.55	0.15	62	2	35	40	0.1	135	AS7-5563a
M-07-39	G37438	93	95	0.47	0.13	34	1.7	35	32	0.1	122	AS7-5563a
M-07-39	G37439	95	97	0.77	0.19	66	2.7	35	40	10	98	AS7-5563a
M-07-39	G37440	97	99	0.60	0.18	37	2.3	40	36	5	105	AS7-5563a
M-07-39	G37441	99	101	0.59	0.18	37	2.5	40	30	5	73	AS7-5563a
M-07-39	G37442	101	103	1.07	0.38	39	5.3	35	44	0.1	113	AS7-5563a
M-07-39	G37443	103	105	0.33	0.09	17	1.7	35	40	5	69	AS7-5563a
M-07-39	G37444	105	107	0.62	0.14	246	2.8	45	74	0.1	44	AS7-5563a
M-07-39	G37445	107	108.3	0.59	0.22	129	3.2	40	40	10	67	AS7-5563a
M-07-39	G37446	108.3	110.2	0.37	0.13	23	2.2	35	32	0.1	43	AS7-5564a
M-07-39	G37447	110.2	112.16	0.47	0.13	22	2.3	30	32	10	48	AS7-5564a
M-07-39	G37448	112.16	114	3.30	0.88	23	9.8	35	40	0.1	12	AS7-5564a
M-07-39	G37449	114	116	0.90	0.29	27	3.5	35	28	0.1	34	AS7-5564a
M-07-39	G37450	116	118	0.24	0.06	21	1	30	30	5	48	AS7-5564a
M-07-39	G37451	118	120	0.38	0.10	22	1.5	30	32	0.1	43	AS7-5564a
M-07-39	G37452	120	122	0.53	0.19	32	2.6	40	26	5	31	AS7-5564a
M-07-39	G37453	122	124	0.30	0.10	29	1.4	30	28	0.1	45	AS7-5564a
M-07-39	G37454	124	126	1.30	0.38	92	4.9	45	30	5	46	AS7-5564a
M-07-39	G37455	126	128	0.34	0.16	12	2	30	28	0.1	42	AS7-5564a
M-07-39	G37457	128	130	0.87	0.29	16	3.8	35	30	0.1	39	AS7-5564a
M-07-39	G37458	130	132	1.09	0.56	16	7.2	30	46	0.1	47	AS7-5564a
M-07-39	G37460	132	134	0.35	0.11	24	1.4	40	26	0.1	48	AS7-5564a
M-07-39	G37461	134	136	0.33	0.12	33	1.7	50	34	0.1	43	AS7-5564a
M-07-39	G37462	136	138	0.38	0.12	27	1.8	30	36	0.1	42	AS7-5564a
M-07-39	G37463	138	140	0.32	0.10	23	1.3	40	32	0.1	47	AS7-5564a
M-07-39	G37464	140	142	0.36	0.11	24	1.5	45	32	0.1	48	AS7-5564a
M-07-39	G37465	142	144	0.93	0.32	79	3.3	35	28	5	42	AS7-5564a
M-07-39	G37466	144	146	0.81	0.25	80	3.4	40	30	5	38	AS7-5564a
M-07-39	G37467	146	147.8	0.95	0.33	37	4.2	45	30	15	30	AS7-5564a
M-07-39	G37468	147.8	150	0.35	0.11	41	1.6	35	34	10	49	AS7-5564a
M-07-39	G37469	150	152	0.34	0.12	42	1.9	50	34	10	53	AS7-5564a
M-07-39	G37470	152	154	0.76	0.15	60	3.8	85	50	0.1	78	AS7-5564a
M-07-39	G37471	154	156	0.75	0.23	13	5.1	40	54	10	67	AS7-5564a
M-07-39	G37473	156	158	0.20	0.05	14	1.3	40	28	5	57	AS7-5564a
M-07-39	G37474	158	160	0.55	0.17	21	2.5	35	30	0.1	55	AS7-5564a
M-07-39	G37475	160	162	0.29	0.10	21	1.5	30	36	0.1	71	AS7-5564a
M-07-39	G37476	162	164	0.43	0.13	32	1.7	30	28	10	57	AS7-5564a
M-07-39	G37477	164	165.3	0.36	0.10	18	1.3	30	28	0.1	51	AS7-5564a
M-07-39	G37478	165.3	166.6	0.53	0.17	18	1.7	30	24	10	52	AS7-5564a
M-07-39	G37479	166.6	168.4	1.80	0.61	12	6.2	35	38	0.1	14	AS7-5564a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-39	G37480	168.4	170.4	1.18	0.39	18	4.3	40	20	0.1	5	AS7-5564a
M-07-39	G37481	170.4	172.3	0.59	0.26	34	2.6	0.1	18	0.1	21	AS7-5566a
M-07-39	G37482	172.3	173.75	0.44	0.12	33	1.5	0.1	20	0.1	35	AS7-5566a
M-07-39	G37483	175.25	176	0.30	0.09	18	1	0.1	18	0.1	29	AS7-5566a
M-07-39	G37484	176	178	0.44	0.15	117	1.8	0.1	22	0.1	27	AS7-5566a
M-07-39	G37485	178	180	0.27	0.07	28	0.8	10	18	0.1	38	AS7-5566a
M-07-39	G37486	180	182	0.25	0.09	52	1.1	10	20	0.1	35	AS7-5566a
M-07-39	G37488	182	184	0.20	0.08	20	1	10	26	0.1	40	AS7-5566a
M-07-39	G37489	184	186	0.55	0.17	34	2	0.1	22	0.1	26	AS7-5566a
M-07-39	G37490	186	188	0.30	0.10	22	1.2	10	18	0.1	33	AS7-5566a
M-07-39	G37491	188	189.7	0.99	0.37	16	4.1	10	18	5	19	AS7-5566a
M-07-39	G37492	191	195.9	0.42	0.13	29	1.6	5	24	0.1	40	AS7-5566a
M-07-39	G37493	195.9	198	0.21	0.08	32	0.8	5	22	5	47	AS7-5566a
M-07-39	G37494	198	200	0.32	0.14	26	1.5	5	22	0.1	50	AS7-5566a
M-07-39	G37495	200	202	0.23	0.10	31	0.9	5	28	0.1	75	AS7-5554a
M-07-39	G37496	202	204	0.16	0.06	21	0.6	10	28	0.1	37	AS7-5566a
M-07-39	G37497	204	206	0.54	0.24	27	2.4	10	42	0.1	60	AS7-5566a
M-07-39	G37498	206	208	0.31	0.10	32	1	10	28	0.1	57	AS7-5566a
M-07-39	G37500	208	210	0.23	0.07	47	1	15	28	5	45	AS7-5566a
M-07-39	G37501	210	212	0.29	0.15	75	1.5	5	28	0.1	42	AS7-5566a
M-07-39	G37502	212	214	0.28	0.10	46	1.1	10	28	0.1	47	AS7-5566a
M-07-39	G37503	214	216	0.31	0.13	41	1.2	5	24	0.1	43	AS7-5566a
M-07-39	G37504	216	218	0.48	0.18	199	1.8	10	26	0.1	46	AS7-5566a
M-07-39	G37506	218	220	0.22	0.07	89	0.9	10	28	0.1	45	AS7-5566a
M-07-39	G37507	220	222	0.16	0.05	42	0.6	0.1	24	0.1	44	AS7-5566a
M-07-39	G37508	222	224	0.14	0.04	36	0.4	10	26	0.1	41	AS7-5566a
M-07-39	G37509	224	226	0.23	0.09	28	0.8	10	26	0.1	36	AS7-5566a
M-07-39	G37510	226	228	0.31	0.11	27	1.2	10	24	0.1	44	AS7-5566a
M-07-39	G37511	228	230	0.32	0.12	29	1.3	10	28	0.1	46	AS7-5566a
M-07-39	G37512	230	232	0.64	0.33	44	2.8	10	54	0.1	55	AS7-5566a
M-07-39	G37513	232	234	0.35	0.13	46	1.6	10	54	5	51	AS7-5566a
M-07-39	G37514	234	236	0.14	0.04	66	0.6	15	36	5	46	AS7-5566a
M-07-39	G37515	236	238	0.16	0.06	45	0.6	15	26	0.1	43	AS7-5566a
M-07-39	G37516	238	240	0.15	0.05	31	0.7	10	16	0.1	47	AS7-5570a
M-07-39	G37517	240	242	0.12	0.04	41	0.6	15	46	0.1	59	AS7-5570a
M-07-39	G37518	242	244	0.16	0.06	24	0.7	5	14	0.1	41	AS7-5570a
M-07-39	G37519	244	246	0.09	0.04	29	0.5	10	12	0.1	45	AS7-5570a
M-07-39	G37520	246	248	0.18	0.04	28	0.7	15	12	0.1	45	AS7-5570a
M-07-39	G37521	248	250	0.25	0.11	69	1.4	10	20	0.1	47	AS7-5570a
M-07-39	G37522	250	252	0.38	0.13	44	1.5	15	12	0.1	51	AS7-5570a
M-07-39	G37523	252	254	0.39	0.15	62	1.4	15	14	0.1	40	AS7-5570a
M-07-39	G37524	254	256	0.23	0.08	61	0.9	10	20	0.1	61	AS7-5570a
M-07-39	G37525	256	257.35	0.39	0.14	174	1.3	15	18	0.1	53	AS7-5570a
M-07-39	G37527	257.35	258.85	0.64	0.19	227	1.8	10	16	0.1	39	AS7-5570a
M-07-39	G37528	258.85	260.2	0.38	0.20	64	1.7	5	22	0.1	17	AS7-5570a
M-07-39	G37529	260.2	262	0.70	0.26	51	2.4	10	12	0.1	37	AS7-5570a
M-07-39	G37530	262	264	0.36	0.13	71	1.3	15	12	0.1	42	AS7-5570a
M-07-39	G37531	264	266	0.16	0.08	42	0.7	10	14	0.1	37	AS7-5570a
M-07-39	G37532	266	268	0.15	0.05	41	0.6	15	8	0.1	43	AS7-5570a
M-07-39	G37533	268	270	0.32	0.08	57	0.9	10	40	0.1	45	AS7-5570a
M-07-39	G37534	270	272	0.17	0.07	42	0.8	10	14	0.1	49	AS7-5570a
M-07-39	G37536	272	274	0.25	0.07	55	0.8	10	20	0.1	59	AS7-5570a
M-07-39	G37537	274	276	0.18	0.08	72	0.8	10	14	0.1	50	AS7-5570a
M-07-39	G37538	276	278	0.25	0.09	32	1	15	12	0.1	60	AS7-5570a
M-07-39	G37539	278	280	0.51	0.22	177	2.2	10	26	0.1	40	AS7-5570a
M-07-39	G37540	280	282	0.15	0.05	27	0.7	10	24	0.1	74	AS7-5570a
M-07-39	G37541	282	284	0.18	0.08	60	0.8	10	18	0.1	62	AS7-5570a
M-07-39	G37542	284	285.89	0.30	0.09	55	1.3	15	24	0.1	56	AS7-5570a
M-07-40	E192557	1.9	13	0.19	0.07	38	0.9	0.1	28	5	53	AS7-5565a
M-07-40	E192558	13	15	0.22	0.08	30	1	0.1	32	15	58	AS7-5565a
M-07-40	E192559	15	17	0.16	0.06	20	0.7	0.1	28	0.1	60	AS7-5565a
M-07-40	E192560	17	19	0.20	0.06	23	0.9	5	36	15	81	AS7-5565a
M-07-40	E192561	19	21	0.33	0.08	29	1.2	0.1	32	10	79	AS7-5565a
M-07-40	E192562	21	23	0.74	0.07	36	1	0.1	30	5	70	AS7-5565a
M-07-40	E192563	23	25	0.48	0.17	88	1.8	0.1	32	15	62	AS7-5565a
M-07-40	E192565	25	27	0.53	0.10	34	1.3	0.1	30	10	54	AS7-5565a
M-07-40	E192566	27	29	0.27	0.08	45	1.1	0.1	30	5	58	AS7-5565a
M-07-40	E192567	29	31	0.23	0.08	41	1.2	0.1	36	10	70	AS7-5565a
M-07-40	E192568	31	33	0.26	0.09	125	1.3	0.1	68	10	105	AS7-5565a
M-07-40	E192570	33	35	0.45	0.09	54	13.9	10	104	15	81	AS7-5565a
M-07-40	E192571	35	37	0.57	0.08	47	1.6	0.1	36	5	86	AS7-5565a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-40	E192572	37	39	0.16	0.06	36	1.9	10	40	15	66	AS7-5565a
M-07-40	E192573	39	41	0.33	0.11	46	6.1	10	162	0.1	149	AS7-5565a
M-07-40	E192574	41	43	0.18	0.07	44	1.6	0.1	74	5	111	AS7-5565a
M-07-40	E192575	43	45	0.38	0.07	39	1.4	0.1	132	10	335	AS7-5565a
M-07-40	E192576	45	47	0.25	0.07	22	0.9	15	404	5	175	AS7-5567a
M-07-40	E192577	47	49	0.27	0.09	128	1	15	68	5	88	AS7-5567a
M-07-40	E192578	49	51	0.28	0.09	88	0.9	10	30	5	56	AS7-5567a
M-07-40	E192579	51	53	0.20	0.07	67	0.6	10	30	0.1	60	AS7-5567a
M-07-40	E192580	53	55	0.35	0.13	39	4.3	15	36	5	58	AS7-5567a
M-07-40	E192581	55	57	0.23	0.07	53	0.8	20	32	5	70	AS7-5567a
M-07-40	E192582	57	59	0.25	0.08	83	1	10	36	5	73	AS7-5567a
M-07-40	E192584	59	61	0.29	0.11	151	1.2	20	36	10	53	AS7-5567a
M-07-40	E192585	61	63	0.21	0.08	63	1	15	30	5	48	AS7-5567a
M-07-40	E192586	63	65	0.30	0.09	62	1.1	10	28	10	46	AS7-5567a
M-07-40	E192587	65	67	0.13	0.05	27	0.8	15	30	10	50	AS7-5567a
M-07-40	E192588	67	69	0.13	0.05	35	0.6	30	52	15	50	AS7-5567a
M-07-40	E192589	69	71	0.13	0.05	25	1.2	30	56	15	62	AS7-5567a
M-07-40	E192590	71	73	0.67	0.22	93	3.8	15	32	0.1	66	AS7-5567a
M-07-40	E192591	73	75	0.27	0.09	56	4.8	20	198	0.1	335	AS7-5567a
M-07-40	E192592	75	77	0.83	0.37	297	3.8	20	36	5	37	AS7-5567a
M-07-40	E192593	77	79	0.34	0.13	148	1.4	20	24	0.1	31	AS7-5567a
M-07-40	E192594	79	81	0.27	0.08	44	1.7	15	38	10	62	AS7-5567a
M-07-40	E192595	81	83	0.20	0.09	77	1.1	20	32	0.1	64	AS7-5567a
M-07-40	E192597	83	85	0.36	0.11	60	1.6	20	34	0.1	53	AS7-5567a
M-07-40	E192598	85	87	0.47	0.13	60	2.5	15	40	0.1	66	AS7-5567a
M-07-40	E192599	87	89	0.49	0.12	58	1.8	30	34	0.1	47	AS7-5567a
M-07-40	E192600	89	91	0.25	0.09	48	1.2	15	30	5	63	AS7-5567a
M-07-40	E192601	91	93	0.29	0.09	64	1.4	20	62	0.1	91	AS7-5567a
M-07-40	E192602	93	95	0.60	0.16	60	7.6	15	116	0.1	175	AS7-5567a
M-07-40	E192603	95	97	0.45	0.14	81	2.8	15	44	5	73	AS7-5567a
M-07-40	E192604	97	99	0.33	0.08	60	1.3	15	30	15	51	AS7-5567a
M-07-40	E192605	99	101	0.27	0.09	74	1	20	38	0.1	45	AS7-5567a
M-07-40	E192607	101	103	0.33	0.12	74	1.2	25	46	0.1	59	AS7-5567a
M-07-40	E192608	103	105	0.29	0.10	57	1.1	20	30	5	55	AS7-5567a
M-07-40	E192609	105	107	0.28	0.08	81	1.1	35	48	0.1	56	AS7-5567a
M-07-40	E192610	107	109	0.28	0.12	90	1.7	20	50	0.1	66	AS7-5567a
M-07-40	E192611	109	111	0.35	0.15	105	1.8	0.1	38	10	64	AS7-5568a
M-07-40	E192612	111	113	0.23	0.07	46	0.8	20	48	5	57	AS7-5568a
M-07-40	E192613	113	115	0.35	0.10	60	1	15	252	0.1	267	AS7-5568a
M-07-40	E192614	115	117	0.33	0.07	134	0.8	10	40	10	63	AS7-5568a
M-07-40	E192615	117	119	0.19	0.05	40	0.6	10	38	5	55	AS7-5568a
M-07-40	E192616	119	121	0.27	0.09	82	1.1	5	46	5	68	AS7-5568a
M-07-40	E192617	121	123	0.24	0.12	75	1.4	20	60	5	74	AS7-5568a
M-07-40	E192619	123	125	0.21	0.11	276	0.9	15	46	0.1	68	AS7-5568a
M-07-40	E192620	125	127	0.22	0.07	145	0.9	20	56	0.1	92	AS7-5568a
M-07-40	E192621	127	129	0.21	0.06	140	0.6	10	42	10	96	AS7-5568a
M-07-40	E192622	129	131	0.18	0.05	77	0.6	20	44	0.1	54	AS7-5568a
M-07-40	E192623	131	133	0.12	0.05	45	0.5	15	38	0.1	48	AS7-5568a
M-07-40	E192624	133	135	0.13	0.05	136	0.4	10	40	0.1	54	AS7-5568a
M-07-40	E192625	135	137	0.13	0.07	121	0.7	30	56	5	76	AS7-5568a
M-07-40	E192626	137	139	0.12	0.06	231	0.6	10	36	0.1	48	AS7-5568a
M-07-40	E192627	139	141	0.23	0.10	158	0.9	15	40	0.1	59	AS7-5568a
M-07-40	E192628	141	143	0.31	0.11	128	1.2	15	40	0.1	62	AS7-5568a
M-07-40	E192629	143	145	0.31	0.09	106	1.4	20	48	5	87	AS7-5568a
M-07-40	E192630	145	147	0.28	0.08	88	1.2	40	46	5	51	AS7-5568a
M-07-40	E192631	147	149	0.21	0.08	98	1.2	40	38	0.1	49	AS7-5568a
M-07-40	E192632	149	151	0.12	0.07	146	0.7	35	32	5	33	AS7-5568a
M-07-40	E192633	151	153	0.17	0.07	285	0.6	25	30	0.1	39	AS7-5568a
M-07-40	E192634	153	155	0.26	0.09	176	0.9	20	30	0.1	37	AS7-5568a
M-07-40	E192636	155	157	0.30	0.11	387	1.2	30	34	0.1	44	AS7-5568a
M-07-40	E192637	157	159	0.35	0.17	278	2.1	35	78	0.1	78	AS7-5568a
M-07-40	E192638	159	161	0.32	0.12	223	1.5	25	36	0.1	80	AS7-5568a
M-07-40	E192639	161	163	0.27	0.11	718	1.3	55	44	0.1	47	AS7-5568a
M-07-40	E192640	163	165	0.19	0.09	124	0.8	25	32	0.1	35	AS7-5568a
M-07-40	E192641	165	167	0.35	0.13	174	1.4	25	36	5	46	AS7-5568a
M-07-40	E192642	167	169	0.38	0.11	168	1.6	30	44	5	74	AS7-5568a
M-07-40	E192643	169	171	0.22	0.08	125	1.2	25	44	15	62	AS7-5568a
M-07-40	E192644	171	173	0.18	0.08	299	1.2	25	44	5	57	AS7-5568a
M-07-40	E192645	173	175	0.35	0.20	214	5.3	35	284	0.1	298	AS7-5568a
M-07-40	E192646	175	177	0.25	0.08	139	0.8	10	10	0.1	29	AS7-5571a
M-07-40	E192647	177	179	0.29	0.11	225	1.3	10	22	0.1	70	AS7-5571a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-40	E192648	179	181	0.35	0.13	97	1.4	10	12	0.1	25	AS7-5571a
M-07-40	E192649	181	183	0.35	0.13	141	1.2	10	7	0.1	24	AS7-5571a
M-07-40	E192650	183	185	0.43	0.14	172	2	15	12	0.1	25	AS7-5571a
M-07-40	E192651	185	187	0.38	0.14	97	2.2	15	14	0.1	24	AS7-5571a
M-07-40	E192652	187	189	0.25	0.09	82	1	10	7	0.1	27	AS7-5571a
M-07-40	E192653	189	191	0.35	0.08	248	1	10	10	0.1	25	AS7-5571a
M-07-40	E192654	191	193	0.24	0.10	104	1.1	10	10	0.1	24	AS7-5571a
M-07-40	E192655	193	195	0.52	0.15	115	2.3	10	7	0.1	21	AS7-5571a
M-07-40	E192656	195	197	0.35	0.09	304	3	15	7	0.1	21	AS7-5571a
M-07-40	E192657	197	199.25	0.60	0.11	95	3.2	35	10	0.1	22	AS7-5571a
M-07-40	E192658	199.25	201	0.41	0.13	82	2.4	10	10	0.1	27	AS7-5571a
M-07-40	E192659	201	203	0.32	0.13	116	5.7	15	14	0.1	27	AS7-5571a
M-07-40	E192661	203	205	0.86	0.11	103	3.9	40	26	0.1	52	AS7-5571a
M-07-40	E192662	205	207	0.50	0.13	112	6.6	25	41	0.1	52	AS7-5571a
M-07-40	E192663	207	209	0.36	0.13	113	7.5	15	166	0.1	63	AS7-5571a
M-07-40	E192664	209	211	0.16	0.09	189	1.2	10	12	0.1	39	AS7-5571a
M-07-40	E192665	211	216	0.20	0.14	68	1.1	10	14	0.1	28	AS7-5571a
M-07-40	E192666	216	220	0.25	0.07	44	0.5	10	10	0.1	31	AS7-5571a
M-07-40	E192667	220	222.65	0.09	0.07	43	0.7	15	14	0.1	34	AS7-5571a
M-07-40	E192668	222.65	224	0.18	0.09	59	0.6	15	12	0.1	28	AS7-5571a
M-07-40	E192669	224	226	0.19	0.14	145	1.3	10	22	0.1	29	AS7-5571a
M-07-40	E192671	226	228	0.13	0.12	246	0.9	15	19	0.1	46	AS7-5571a
M-07-40	E192672	228	230	0.16	0.11	57	0.7	15	14	0.1	29	AS7-5571a
M-07-40	E192673	230	232	0.06	0.07	95	0.6	20	14	0.1	67	AS7-5571a
M-07-40	E192674	232	233.55	0.06	0.00	3	0.01	60	48	0.1	111	AS7-5571a
M-07-40	E192675	233.55	235	0.13	0.01	7	0.5	45	19	0.1	43	AS7-5571a
M-07-40	E192677	235	237	0.13	0.01	2	1.1	20	12	0.1	45	AS7-5571a
M-07-40	E192678	237	239	0.30	0.00	5	1.4	20	60	0.1	64	AS7-5571a
M-07-40	E192679	239	241	0.16	0.01	3	1	25	26	0.1	59	AS7-5571a
M-07-40	E192680	241	243	0.11	0.01	7	0.6	15	26	0.1	48	AS7-5571a
M-07-40	E192681	243	245	0.09	0.00	6	0.6	15	42	0.1	66	AS7-5589a
M-07-40	E192682	245	247	0.06	0.01	8	0.5	10	26	0.1	68	AS7-5589a
M-07-40	E192683	247	249	0.06	0.00	7	0.4	15	16	0.1	59	AS7-5589a
M-07-40	E192684	249	251.14	0.25	0.00	10	1.5	20	18	0.1	52	AS7-5589a
M-07-41	G37543	6.75	8	0.19	0.06	36	0.6	10	12	0.1	37	AS7-5570a
M-07-41	G37544	8	10	0.20	0.06	42	0.8	10	14	0.1	31	AS7-5570a
M-07-41	G37545	10	12	0.30	0.08	84	0.9	15	12	0.1	45	AS7-5570a
M-07-41	G37546	12	14	0.19	0.08	62	1.1	20	16	0.1	54	AS7-5570a
M-07-41	G37547	14	16	0.14	0.06	65	0.7	30	34	0.1	120	AS7-5570a
M-07-41	G37548	16	18	0.46	0.18	44	2	30	18	0.1	77	AS7-5570a
M-07-41	G37549	18	20	0.66	0.20	36	1.9	20	14	0.1	70	AS7-5570a
M-07-41	G37550	20	22	0.67	0.17	28	1.7	25	18	0.1	60	AS7-5570a
M-07-41	G37551	22	24	0.43	0.09	42	1	30	48	5	90	AS7-5569a
M-07-41	G37552	24	26	0.34	0.13	31	1.3	20	56	0.1	78	AS7-5569a
M-07-41	G37553	26	28	0.48	0.15	38	1.5	30	44	5	69	AS7-5569a
M-07-41	G37554	28	30	0.65	0.13	35	1.5	30	46	5	83	AS7-5569a
M-07-41	G37555	30	32	0.55	0.13	31	1.3	30	44	5	101	AS7-5569a
M-07-41	G37556	32	34	0.40	0.12	46	1.6	20	50	0.1	107	AS7-5569a
M-07-41	G37557	34	36	0.33	0.12	48	1.4	25	48	0.1	119	AS7-5569a
M-07-41	G37558	36	38	0.54	0.13	41	1.6	25	48	15	92	AS7-5569a
M-07-41	G37559	38	40	0.38	0.14	33	1.8	15	44	5	101	AS7-5569a
M-07-41	G37560	40	42	0.38	0.13	74	1.3	25	38	5	104	AS7-5569a
M-07-41	G37562	42	44	0.40	0.12	60	1.3	40	38	0.1	82	AS7-5569a
M-07-41	G37563	44	46	0.29	0.12	38	1.4	20	42	5	83	AS7-5569a
M-07-41	G37564	46	48	0.60	0.22	54	2.4	25	40	0.1	87	AS7-5569a
M-07-41	G37565	48	50	0.26	0.08	32	0.9	45	64	15	104	AS7-5569a
M-07-41	G37566	50	52	0.00	0.01	5	0.01	60	100	25	89	AS7-5569a
M-07-41	G37567	52	54	0.25	0.06	47	0.8	35	94	20	225	AS7-5569a
M-07-41	G37568	54	56	0.08	0.01	7	0.2	45	162	25	296	AS7-5569a
M-07-41	G37569	56	58	0.00	0.01	6	0.01	60	110	25	97	AS7-5569a
M-07-41	G37570	58	60	0.00	0.01	6	0.01	50	106	20	106	AS7-5569a
M-07-41	G37571	60	62	0.00	0.01	6	0.5	55	106	25	106	AS7-5569a
M-07-41	G37572	62	64	0.08	0.04	16	0.4	50	82	15	102	AS7-5569a
M-07-41	G37573	64	66	0.28	0.10	42	1.3	40	42	0.1	83	AS7-5569a
M-07-41	G37574	66	68	0.30	0.10	44	1.4	40	40	5	70	AS7-5569a
M-07-41	G37575	68	70	0.20	0.07	39	0.8	40	82	20	135	AS7-5569a
M-07-41	G37576	70	72	0.24	0.09	63	1.3	40	66	10	94	AS7-5569a
M-07-41	G37577	72	74	0.36	0.13	82	1.8	40	88	10	82	AS7-5569a
M-07-41	G37578	74	76	0.33	0.11	63	1.4	35	50	0.1	90	AS7-5569a
M-07-41	G37579	76	78	0.26	0.11	58	1.6	40	48	15	93	AS7-5569a
M-07-41	G37581	78	80	0.57	0.20	79	2.3	50	44	0.1	79	AS7-5569a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-41	G37582	80	82	0.26	0.09	47	1.3	60	44	5	113	AS7-5569a
M-07-41	G37583	82	84	0.10	0.04	47	0.9	40	54	0.1	42	AS7-5569a
M-07-41	G37584	84	86	0.13	0.05	34	0.9	45	82	0.1	69	AS7-5569a
M-07-41	G37586	86	88	0.07	0.04	14	0.7	0.1	40	10	49	AS7-5572a
M-07-41	G37587	88	90	0.13	0.03	14	0.4	0.1	38	25	78	AS7-5572a
M-07-41	G37588	90	92	0.08	0.03	10	0.5	0.1	46	10	38	AS7-5572a
M-07-41	G37589	92	94	0.08	0.02	12	0.2	0.1	38	10	44	AS7-5572a
M-07-41	G37590	94	96	0.08	0.02	7	0.2	0.1	32	20	56	AS7-5572a
M-07-41	G37591	96	98	0.07	0.02	8	0.3	0.1	34	10	51	AS7-5572a
M-07-41	G37592	98	100	0.11	0.02	9	0.4	0.1	36	10	47	AS7-5572a
M-07-41	G37593	100	102	0.10	0.01	7	0.3	0.1	42	10	38	AS7-5572a
M-07-41	G37594	102	104	0.06	0.01	7	0.4	0.1	42	10	37	AS7-5572a
M-07-41	G37595	104	106	0.05	0.02	9	0.4	0.1	58	15	39	AS7-5572a
M-07-41	G37596	106	108	0.13	0.02	10	0.4	0.1	40	20	61	AS7-5572a
M-07-41	G37597	108	110	0.16	0.02	9	0.3	0.1	52	15	60	AS7-5572a
M-07-41	G37598	110	112	0.08	0.01	9	0.2	0.1	40	20	47	AS7-5572a
M-07-41	G37599	112	114.3	0.10	0.01	11	0.2	0.1	46	20	45	AS7-5572a
M-07-41	G37602	114.3	116	0.11	0.03	11	0.4	5	58	20	172	AS7-5572a
M-07-41	G37603	116	118	0.06	0.01	13	0.8	10	72	35	65	AS7-5572a
M-07-41	G37604	118	120	0.07	0.01	7	1.8	25	76	50	53	AS7-5572a
M-07-41	G37605	120	122	0.08	0.01	10	3.4	20	132	50	176	AS7-5572a
M-07-41	G37606	122	124	0.12	0.01	9	2.6	0.1	134	40	85	AS7-5572a
M-07-41	G37607	124	126.2	0.08	0.01	10	1.5	10	110	25	62	AS7-5572a
M-07-41	G37608	126.2	128.4	0.12	0.03	6	0.3	20	30	25	89	AS7-5572a
M-07-41	G37609	128.4	130	0.04	0.02	9	0.3	15	42	25	52	AS7-5572a
M-07-41	G37610	130	132	0.05	0.01	7	0.4	0.1	42	15	35	AS7-5572a
M-07-41	G37611	132	134	0.06	0.02	5	0.6	0.1	46	5	31	AS7-5572a
M-07-41	G37612	134	135.6	0.07	0.03	6	1.1	0.1	72	0.1	121	AS7-5572a
M-07-41	G37613	135.6	138	0.11	0.03	7	1.4	10	50	25	70	AS7-5572a
M-07-41	G37614	138	140.2	0.17	0.03	4	1.6	5	42	10	37	AS7-5572a
M-07-41	G37615	140.2	142	0.19	0.03	8	1.6	0.1	48	15	30	AS7-5572a
M-07-41	G37616	142	144.3	0.13	0.06	3	1	10	30	0.1	31	AS7-5572a
M-07-41	G37617	144.3	146	0.21	0.04	6	1	10	32	15	72	AS7-5572a
M-07-41	G37618	146	148	0.13	0.02	4	0.4	15	34	15	63	AS7-5572a
M-07-41	G37619	148	150	0.12	0.01	6	0.5	10	38	15	51	AS7-5572a
M-07-41	G37620	150	152	0.08	0.03	6	0.6	15	30	20	58	AS7-5572a
M-07-41	G37621	152	154	0.13	0.02	2	1	20	22	0.1	71	AS7-5574a
M-07-41	G37622	154	156	0.14	0.05	2	1.3	25	18	0.1	106	AS7-5574a
M-07-41	G37624	156	158	0.12	0.04	1	1.7	20	64	0.1	65	AS7-5574a
M-07-41	G37625	158	160.1	0.19	0.05	2	1.9	15	30	0.1	44	AS7-5574a
M-07-41	G37626	160.1	162	0.06	0.02	5	0.6	5	12	0.1	13	AS7-5574a
M-07-41	G37627	162	164	0.18	0.03	2	1.3	10	26	0.1	44	AS7-5574a
M-07-41	G37628	164	166	0.14	0.04	2	0.9	20	24	0.1	66	AS7-5574a
M-07-41	G37629	166	168	0.25	0.04	0.1	0.5	25	18	0.1	80	AS7-5574a
M-07-41	G37630	168	170	0.22	0.04	0.1	0.6	25	20	0.1	68	AS7-5574a
M-07-41	G37632	170	172	0.42	0.09	0.1	0.6	20	20	0.1	65	AS7-5574a
M-07-41	G37633	172	174	0.27	0.11	5	0.7	20	16	0.1	43	AS7-5574a
M-07-41	G37634	174	176	0.17	0.19	2	1.2	25	22	0.1	59	AS7-5574a
M-07-41	G37635	176	178	0.11	0.08	3	0.9	15	30	0.1	69	AS7-5574a
M-07-41	G37636	178	180	0.12	0.06	23	1.2	20	36	0.1	480	AS7-5574a
M-07-41	G37637	180	182	0.12	0.15	2	1.8	30	48	5	71	AS7-5574a
M-07-41	G37638	182	184.6	0.11	0.06	2	1.4	15	28	0.1	54	AS7-5574a
M-07-41	G37639	184.6	186	0.07	0.02	1	2	15	24	0.1	75	AS7-5574a
M-07-41	G37640	186	187.4	0.08	0.03	2	1	15	24	0.1	407	AS7-5574a
M-07-41	G37641	187.4	190	0.05	0.03	1	0.7	20	20	0.1	328	AS7-5574a
M-07-41	G37643	190	192.6	0.09	0.02	4	0.2	20	20	0.1	81	AS7-5574a
M-07-41	G37644	192.6	194	0.08	0.01	0.1	0.5	25	82	0.1	119	AS7-5574a
M-07-41	G37645	194	196	0.10	0.03	3	0.9	25	76	0.1	256	AS7-5574a
M-07-41	G37646	196	197.81	0.06	0.02	1	0.2	25	20	0.1	103	AS7-5574a
M-07-42	G35301	2.13	4	0.29	0.07	2	1.5	15	36	0.1	54	AS7-5573a
M-07-42	G35302	4	6	0.39	0.12	1	3.1	35	88	0.1	87	AS7-5573a
M-07-42	G35303	6	8	1.21	0.06	2	7.6	85	368	0.1	400	AS7-5573a
M-07-42	G35304	8	10	0.60	0.12	2	2.4	35	26	0.1	75	AS7-5573a
M-07-42	G35305	10	11.5	0.35	0.05	3	1.5	25	18	0.1	49	AS7-5573a
M-07-42	G35306	11.5	12.8	0.31	0.08	5	2.4	25	14	0.1	51	AS7-5573a
M-07-42	G35307	14.6	16	0.29	0.07	0.1	1.3	15	8	0.1	134	AS7-5573a
M-07-42	G35309	16	18	0.34	0.10	0.1	2.1	15	16	0.1	86	AS7-5573a
M-07-42	G35310	18	20	0.30	0.12	1	2.6	15	20	0.1	80	AS7-5573a
M-07-42	G35311	20	22	0.19	0.16	0.1	2	15	14	0.1	58	AS7-5573a
M-07-42	G35312	22	23.1	0.14	0.14	0.1	1.4	10	14	0.1	53	AS7-5573a
M-07-42	G35313	23.1	25	0.05	0.05	2	0.9	10	12	0.1	3	AS7-5573a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-42	G35314	25	26	0.20	0.12	2	2.1	15	12	0.1	21	AS7-5573a
M-07-42	G35315	26	28	0.35	0.14	0.1	1.9	20	12	0.1	43	AS7-5573a
M-07-42	G35316	28	30	0.31	0.11	0.1	1.7	15	14	0.1	61	AS7-5573a
M-07-42	G35317	30	31.5	0.37	0.09	0.1	1.6	15	18	0.1	82	AS7-5573a
M-07-42	G35319	31.5	32.4	0.26	0.14	0.1	1.4	10	20	0.1	59	AS7-5573a
M-07-42	G35320	32.4	33.9	0.32	0.16	0.1	1.6	15	22	0.1	66	AS7-5573a
M-07-42	G35321	33.9	35.4	1.08	0.09	0.1	1.7	15	18	0.1	89	AS7-5573a
M-07-42	G35322	35.4	36.85	0.48	0.09	2	2.9	20	42	0.1	114	AS7-5573a
M-07-42	G35323	36.85	39	0.40	0.12	1	1.8	20	16	0.1	72	AS7-5573a
M-07-42	G35324	39	41	0.32	0.13	1	2.8	20	22	0.1	75	AS7-5573a
M-07-42	G35325	41	43	0.48	0.09	1	2.5	15	22	0.1	91	AS7-5573a
M-07-42	G35326	43	45	0.09	0.05	2	1	10	10	0.1	54	AS7-5573a
M-07-42	G35328	45	47	0.31	0.08	0.1	1.1	15	14	0.1	55	AS7-5573a
M-07-42	G35329	47	49	0.33	0.11	2	1.6	15	12	0.1	58	AS7-5573a
M-07-42	G35330	49	51	0.27	0.17	3	1.8	15	14	0.1	42	AS7-5573a
M-07-42	G35331	51	53	0.18	0.14	2	1.3	10	12	0.1	47	AS7-5573a
M-07-42	G35332	53	55	0.13	0.08	2	1	15	12	0.1	47	AS7-5573a
M-07-42	G35333	55	56.55	0.17	0.07	2	0.7	10	10	0.1	46	AS7-5573a
M-07-42	G35334	56.55	58	0.16	0.08	1	1.6	15	16	0.1	64	AS7-5573a
M-07-42	G35335	58	60	0.14	0.14	2	1.3	10	14	0.1	55	AS7-5573a
M-07-42	G35336	60	62	0.30	0.18	0.1	1.2	10	14	0.1	49	AS7-5576a
M-07-42	G35337	62	64	0.15	0.15	2	1.1	5	12	0.1	48	AS7-5576a
M-07-42	G35338	64	66	0.09	0.14	2	1	5	10	0.1	49	AS7-5576a
M-07-42	G35339	66	68	0.24	0.13	1	1.5	10	12	0.1	72	AS7-5576a
M-07-42	G35340	68	69.1	0.12	0.12	2	1.4	10	12	0.1	72	AS7-5576a
M-07-42	G35341	69.1	70.3	0.19	0.14	2	1.7	10	12	0.1	65	AS7-5576a
M-07-42	G35342	70.3	72	0.23	0.23	3	2.5	10	14	0.1	51	AS7-5576a
M-07-42	G35343	72	74	0.16	0.17	1	2	10	22	0.1	163	AS7-5576a
M-07-42	G35345	74	76	0.15	0.17	2	1.5	15	12	0.1	47	AS7-5576a
M-07-42	G35346	76	78	0.13	0.15	1	1.7	15	16	0.1	90	AS7-5576a
M-07-42	G35347	78	80	0.20	0.16	2	1	20	12	0.1	55	AS7-5576a
M-07-42	G35348	80	82	0.11	0.16	1	1.1	20	28	0.1	154	AS7-5576a
M-07-42	G35349	82	84	0.09	0.12	2	1.1	25	28	0.1	225	AS7-5576a
M-07-42	G35350	84	86	0.06	0.12	1	1.4	40	68	0.1	750	AS7-5576a
M-07-42	G35351	86	87.2	0.07	0.09	2	1.7	15	120	0.1	1914	AS7-5576a
M-07-42	G35352	87.2	89	0.12	0.13	0.1	3.7	15	16	0.1	92	AS7-5576a
M-07-42	G35353	89	91	0.04	0.09	2	1.9	10	12	0.1	119	AS7-5576a
M-07-42	G35354	91	93	0.08	0.09	1	0.7	10	14	0.1	130	AS7-5576a
M-07-42	G35355	93	95	0.10	0.14	2	1.8	15	14	0.1	323	AS7-5576a
M-07-42	G35356	95	97	0.08	0.11	1	1	10	14	0.1	93	AS7-5576a
M-07-42	G35358	97	98.9	0.18	0.13	0.1	1.2	10	12	0.1	82	AS7-5576a
M-07-42	G35359	98.9	101	0.18	0.19	3	1.5	30	26	0.1	256	AS7-5576a
M-07-42	G35360	101	103	0.23	0.17	3	1.7	10	32	0.1	244	AS7-5576a
M-07-42	G35361	103	105	0.14	0.23	4	3.6	15	156	0.1	7496	AS7-5576a
M-07-42	G35362	105	107	0.10	0.14	3	2	15	40	0.1	385	AS7-5576a
M-07-42	G35363	107	109	0.10	0.15	4	2.1	10	44	0.1	83	AS7-5576a
M-07-42	G35364	109	111	0.10	0.24	2	2.7	20	24	0.1	80	AS7-5576a
M-07-42	G35366	111	113	0.06	0.10	3	1.1	10	10	0.1	62	AS7-5576a
M-07-42	G35367	113	114.9	0.11	0.13	2	1.4	20	34	0.1	94	AS7-5576a
M-07-42	G35368	114.9	116.5	0.07	0.07	3	1	15	42	0.1	51	AS7-5576a
M-07-42	G35369	116.5	118.2	0.06	0.08	3	1.6	30	44	0.1	2164	AS7-5576a
M-07-42	G35370	119.5	120.75	0.04	0.08	7	1.1	5	76	0.1	118	AS7-5576a
M-07-42	G35371	120.75	121.8	0.17	0.10	16	0.8	0.1	38	0.1	123	AS7-5579a
M-07-42	G35372	123.5	125.15	0.12	0.10	25	0.7	15	60	20	180	AS7-5579a
M-07-42	G35373	125.65	127	0.14	0.08	8	0.4	10	48	10	73	AS7-5579a
M-07-42	G35374	127	129	0.15	0.12	23	0.6	20	52	5	75	AS7-5579a
M-07-42	G35375	129	131	0.10	0.09	14	0.4	5	44	15	87	AS7-5579a
M-07-42	G35377	131	133	0.18	0.05	9	0.4	0.1	26	0.1	72	AS7-5579a
M-07-42	G35378	133	135	0.14	0.10	6	0.4	10	26	0.1	75	AS7-5579a
M-07-42	G35379	135	137	0.13	0.09	10	0.4	15	32	25	111	AS7-5579a
M-07-42	G35380	137	138.1	0.15	0.08	9	0.5	20	30	10	68	AS7-5579a
M-07-42	G35381	138.1	140	0.23	0.13	18	0.6	20	24	85	68	AS7-5579a
M-07-42	G35382	140	142	0.15	0.08	6	0.6	10	26	10	76	AS7-5579a
M-07-42	G35383	142	144	0.27	0.12	6	0.7	5	24	0.1	49	AS7-5579a
M-07-42	G35384	144	146	0.15	0.17	12	1	15	34	15	83	AS7-5579a
M-07-42	G35385	146	148	0.09	0.09	7	0.5	15	26	10	72	AS7-5579a
M-07-42	G35386	148	150	0.12	0.08	5	0.6	20	24	10	63	AS7-5579a
M-07-42	G35387	150	152	0.08	0.06	5	0.5	10	24	10	94	AS7-5579a
M-07-42	G35388	152	154	0.10	0.11	7	0.9	20	30	10	79	AS7-5579a
M-07-42	G35389	154	156	0.16	0.20	12	1.6	5	34	10	141	AS7-5579a
M-07-42	G35391	156	158	0.16	0.12	8	0.8	30	36	15	145	AS7-5579a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-42	G35392	158	160	0.20	0.12	9	0.8	10	30	25	135	AS7-5579a
M-07-42	G35393	160	162	0.11	0.11	9	0.7	30	28	5	106	AS7-5579a
M-07-42	G35394	162	164	0.16	0.19	33	1.1	25	32	10	128	AS7-5579a
M-07-42	G35395	164	166	0.23	0.12	17	1	15	42	10	103	AS7-5579a
M-07-42	G35396	166	168	0.18	0.09	15	0.6	0.1	30	10	97	AS7-5579a
M-07-42	G35398	168	170	0.09	0.05	14	0.4	10	36	10	104	AS7-5579a
M-07-42	G35399	170	172	0.11	0.08	16	0.9	20	42	15	150	AS7-5579a
M-07-42	G35400	172	174	0.10	0.14	15	1.9	35	42	10	124	AS7-5579a
M-07-42	G35401	174	176	0.14	0.13	26	2.4	10	68	10	318	AS7-5579a
M-07-42	G35402	176	178	0.93	0.12	25	2.6	0.1	106	25	202	AS7-5579a
M-07-42	G35403	178	179.55	0.67	0.03	21	0.6	40	46	50	99	AS7-5579a
M-07-42	G35404	179.55	181	0.36	0.14	19	1.5	80	36	15	79	AS7-5579a
M-07-42	G35405	181	183	0.09	0.13	17	1.4	25	34	25	121	AS7-5579a
M-07-42	G35406	183	185	0.08	0.05	10	1.2	15	56	20	245	AS7-5580a
M-07-42	G35407	185	187	0.13	0.08	12	1.2	10	48	15	238	AS7-5580a
M-07-42	G35408	187	189	0.11	0.06	11	0.8	5	46	20	177	AS7-5580a
M-07-42	G35409	189	191	0.05	0.06	13	0.9	5	52	15	259	AS7-5580a
M-07-42	G35410	191	192	0.10	0.12	30	1.2	20	54	20	297	AS7-5580a
M-07-42	G35411	192	194	0.16	0.13	21	1.3	10	52	45	144	AS7-5580a
M-07-42	G35412	194	196.25	0.15	0.10	9	1.2	0.1	32	20	82	AS7-5580a
M-07-42	G35413	196.25	198	0.16	0.14	15	1.7	0.1	46	10	126	AS7-5580a
M-07-42	G35414	198	200	0.09	0.10	8	1.5	15	36	5	100	AS7-5580a
M-07-42	G35415	200	202	0.11	0.11	9	1.6	10	40	20	87	AS7-5580a
M-07-42	G35417	202	204	0.07	0.08	6	1.3	10	42	10	92	AS7-5580a
M-07-42	G35418	204	205.5	0.23	0.14	11	2.9	10	44	30	85	AS7-5580a
M-07-42	G35419	205.5	207	0.17	0.06	14	3.3	35	76	10	55	AS7-5580a
M-07-42	G35420	207	208.5	0.21	0.05	15	2.4	35	70	0.1	57	AS7-5580a
M-07-42	G35421	208.5	210	0.17	0.09	18	2.2	15	42	10	74	AS7-5580a
M-07-42	G35422	210	212	0.09	0.06	14	0.8	20	46	15	66	AS7-5580a
M-07-42	G35423	212	214	0.15	0.10	10	1	20	50	25	96	AS7-5580a
M-07-42	G35424	214	216	0.12	0.20	14	1.4	20	68	35	94	AS7-5580a
M-07-42	G35425	216	218	0.18	0.12	22	0.7	15	52	25	67	AS7-5580a
M-07-42	G35426	218	220	0.14	0.10	7	0.7	20	42	15	56	AS7-5580a
M-07-42	G35428	220	222	0.30	0.09	15	0.9	20	38	10	67	AS7-5580a
M-07-42	G35429	222	224	0.49	0.12	22	1.2	15	52	25	104	AS7-5580a
M-07-42	G35430	224	226	0.12	0.08	8	1.4	25	104	25	140	AS7-5580a
M-07-42	G35431	226	228	0.18	0.13	16	3.2	30	1170	30	747	AS7-5580a
M-07-42	G35432	228	230	0.11	0.10	7	0.8	30	60	15	87	AS7-5580a
M-07-42	G35433	230	232	0.08	0.08	9	0.6	30	62	20	102	AS7-5580a
M-07-42	G35435	232	233.4	0.12	0.08	9	1.7	25	84	30	127	AS7-5580a
M-07-42	G35436	233.4	234.8	0.21	0.09	8	2.6	30	86	20	96	AS7-5580a
M-07-42	G35437	234.8	236.95	0.10	0.06	6	1.6	35	50	5	62	AS7-5580a
M-07-42	G35438	236.95	238	0.08	0.08	9	1.5	40	44	15	90	AS7-5580a
M-07-42	G35439	238	240	0.08	0.11	9	1.6	35	80	20	184	AS7-5580a
M-07-42	G35440	240	242	0.11	0.08	25	2.9	45	536	15	1638	AS7-5580a
M-07-42	G35441	242	243.6	0.15	0.09	16	3.4	20	174	15	479	AS7-5582a
M-07-42	G35442	243.6	245.6	0.08	0.08	12	2.2	20	132	15	363	AS7-5582a
M-07-42	G35443	245.6	247.6	0.11	0.10	21	2.5	20	130	10	174	AS7-5582a
M-07-42	G35444	247.6	248.7	0.12	0.07	15	3.2	25	124	25	149	AS7-5582a
M-07-42	G35445	248.7	251.25	0.05	0.11	9	2.5	30	440	30	427	AS7-5582a
M-07-42	G35446	253.2	255	0.10	0.09	7	1.8	20	42	0.1	45	AS7-5582a
M-07-42	G35447	255	257	0.33	0.40	27	11.5	35	1890	30	3102	AS7-5582a
M-07-42	G35449	257	259	0.09	0.09	8	2.8	30	202	15	293	AS7-5582a
M-07-42	G35450	259	261	0.13	0.13	7	2.3	30	206	15	387	AS7-5582a
M-07-42	G35451	261	263	0.10	0.10	8	2.1	20	62	30	81	AS7-5582a
M-07-42	G35452	263	265	0.04	0.03	9	1.7	55	230	55	663	AS7-5582a
M-07-42	G35453	265	267	0.05	0.04	8	1.4	40	314	50	511	AS7-5582a
M-07-42	G35454	267	269.2	0.14	0.04	9	1.6	45	170	15	219	AS7-5582a
M-07-42	G35455	269.2	272	0.08	0.06	10	2.1	40	346	20	680	AS7-5582a
M-07-42	G35456	272	273.65	0.03	0.01	46	1.5	55	430	10	1044	AS7-5582a
M-07-42	G35458	274.5	276	0.09	0.05	11	1.8	50	364	25	658	AS7-5582a
M-07-42	G35459	276	278	0.08	0.06	13	3.1	40	232	25	290	AS7-5582a
M-07-42	G35460	278	280	0.06	0.02	19	2	45	386	20	468	AS7-5582a
M-07-42	G35461	280	282	0.11	0.03	20	2.1	50	172	25	371	AS7-5582a
M-07-42	G35462	282	284	0.07	0.03	18	2.4	45	340	40	578	AS7-5582a
M-07-42	G35463	284	286	0.07	0.03	14	2.3	60	326	30	536	AS7-5582a
M-07-42	G35464	286	288	0.10	0.06	26	3.4	65	410	65	1354	AS7-5582a
M-07-42	G35465	288	290	0.07	0.03	29	2.6	35	312	10	282	AS7-5582a
M-07-42	G35466	290	292	0.10	0.03	32	3.8	50	324	10	186	AS7-5582a
M-07-42	G35467	292	294	0.07	0.02	15	2.3	35	106	10	68	AS7-5582a
M-07-42	G35468	294	296	0.10	0.04	9	2.7	30	72	10	79	AS7-5582a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-42	G35469	296	298	0.08	0.02	23	1.9	40	74	20	99	AS7-5582a
M-07-42	G35470	298	300	0.09	0.03	10	1.9	35	82	5	43	AS7-5582a
M-07-42	G35471	300	302	0.10	0.03	19	2.1	35	52	10	39	AS7-5582a
M-07-42	G35472	302	304	0.60	0.03	9	2.6	30	48	10	56	AS7-5582a
M-07-42	G35473	304	306	0.07	0.01	13	1.8	55	42	20	41	AS7-5582a
M-07-42	G35474	306	308	0.11	0.02	8	3.3	30	260	0.1	49	AS7-5582a
M-07-42	G35475	308	310	0.62	0.02	7	3.5	50	172	10	78	AS7-5582a
M-07-42	G35476	310	312	0.08	0.04	14	1.9	35	186	30	128	AS7-5595a
M-07-42	G35477	312	314	0.06	0.02	30	1.2	45	174	10	263	AS7-5595a
M-07-42	G35478	314	316	0.11	0.06	13	1.5	40	176	15	211	AS7-5595a
M-07-42	G35479	316	318	0.12	0.04	9	1.6	45	200	15	257	AS7-5595a
M-07-42	G35480	318	319.5	0.09	0.04	12	2.6	50	520	15	608	AS7-5595a
M-07-42	G35481	319.5	321.1	0.18	0.07	14	3.7	30	472	15	1046	AS7-5595a
M-07-42	G35482	321.1	323	0.21	0.11	24	5.7	30	632	15	4172	AS7-5595a
M-07-42	G35483	323	325	0.03	0.01	5	1	45	194	20	282	AS7-5595a
M-07-42	G35484	325	327	0.04	0.01	4	0.7	45	46	10	54	AS7-5595a
M-07-42	G35486	327	329	0.16	0.02	10	1.2	45	196	20	75	AS7-5595a
M-07-42	G35487	329	331	0.06	0.01	4	0.5	50	58	5	50	AS7-5595a
M-07-42	G35488	331	333	0.17	0.06	11	2.1	50	576	15	278	AS7-5595a
M-07-42	G35489	333	335	0.14	0.06	26	1.4	50	68	20	74	AS7-5595a
M-07-42	G35490	335	337	0.12	0.06	19	1.1	45	58	10	64	AS7-5595a
M-07-42	G35491	337	339	0.11	0.09	27	2.1	50	532	20	344	AS7-5595a
M-07-42	G35493	339	341	0.11	0.08	14	2	50	60	15	84	AS7-5595a
M-07-42	G35494	341	343	0.23	0.15	10	2.6	50	78	20	84	AS7-5595a
M-07-42	G35495	343	345	0.10	0.08	15	1.3	55	58	20	76	AS7-5595a
M-07-42	G35496	345	347	0.18	0.07	16	1.2	45	66	15	66	AS7-5595a
M-07-42	G35497	347	349	0.09	0.04	22	0.9	40	52	20	60	AS7-5595a
M-07-42	G35499	349	351	0.08	0.05	28	1.1	40	312	20	134	AS7-5595a
M-07-42	G35500	351	353	0.08	0.03	30	0.6	40	56	5	72	AS7-5595a
M-07-42	G35501	353	354.5	0.36	0.18	21	2.4	40	62	15	60	AS7-5595a
M-07-42	G35502	354.5	355.68	0.13	0.05	20	0.4	45	66	25	127	AS7-5595a
M-07-43	G37647	1	3	0.91	0.26	55	1.5	35	26	25	73	AS7-5574a
M-07-43	G37648	3	5	0.93	0.23	26	1	15	50	0.1	1058	AS7-5574a
M-07-43	G37649	5	7	1.39	0.20	47	1.1	40	82	10	110	AS7-5574a
M-07-43	G37650	7	9	1.08	0.19	32	9.7	125	44	65	102	AS7-5574a
M-07-43	G37651	9	11	1.20	0.22	142	0.8	30	48	10	107	AS7-5574a
M-07-43	G37652	11	13	0.81	0.17	54	1.1	15	42	0.1	74	AS7-5574a
M-07-43	G37653	13	15	1.17	0.21	63	0.9	15	62	0.1	220	AS7-5574a
M-07-43	G37654	15	17	0.82	0.19	94	1.5	10	32	0.1	296	AS7-5574a
M-07-43	G37655	17	19	1.01	0.17	112	1.2	15	36	0.1	215	AS7-5574a
M-07-43	G37656	19	21	0.55	0.16	53	1.2	15	76	0.1	80	AS7-5575a
M-07-43	G37657	21	23.7	0.76	0.13	70	1.1	15	60	0.1	153	AS7-5575a
M-07-43	G37658	23.7	25.6	0.92	0.16	83	1.2	15	34	0.1	126	AS7-5575a
M-07-43	G37659	25.6	27.7	1.08	0.07	56	1.5	45	38	0.1	325	AS7-5575a
M-07-43	G37660	27.7	30	0.53	0.14	117	1.1	30	26	25	63	AS7-5575a
M-07-43	G37661	30	32	0.70	0.15	150	1.4	170	22	150	106	AS7-5575a
M-07-43	G37662	32	34	0.43	0.09	70	1.1	170	20	100	81	AS7-5575a
M-07-43	G37663	34	36	0.67	0.13	102	0.9	120	50	70	146	AS7-5575a
M-07-43	G37664	36	38	0.52	0.13	49	0.9	130	30	110	167	AS7-5575a
M-07-43	G37665	38	40	0.45	0.13	72	0.8	90	42	75	193	AS7-5575a
M-07-43	G37666	40	42	0.28	0.04	85	0.3	40	72	25	385	AS7-5575a
M-07-43	G37667	42	44	0.63	0.17	95	0.9	85	64	45	266	AS7-5575a
M-07-43	G37668	44	46	0.34	0.14	72	0.8	70	50	40	337	AS7-5575a
M-07-43	G37670	46	46	0.31	0.10	129	0.5	45	118	10	220	AS7-5575a
M-07-43	G37671	48	50	0.29	0.08	69	0.7	55	106	15	1911	AS7-5575a
M-07-43	G37672	50	52	0.37	0.13	65	0.5	25	72	5	108	AS7-5575a
M-07-43	G37673	52	54	0.42	0.12	75	0.8	55	100	5	164	AS7-5575a
M-07-43	G37674	54	56	0.25	0.12	61	0.9	15	24	5	28	AS7-5575a
M-07-43	G37675	56	58	0.24	0.15	38	1.2	140	24	45	45	AS7-5575a
M-07-43	G37676	58	60	0.24	0.12	42	1	270	30	30	87	AS7-5575a
M-07-43	G37677	60	62	0.50	0.16	163	0.8	240	52	15	104	AS7-5575a
M-07-43	G37678	62	64	0.42	0.11	54	0.9	45	32	5	243	AS7-5575a
M-07-43	G37679	64	66	0.47	0.11	71	0.6	10	22	0.1	179	AS7-5575a
M-07-43	G37682	66	68	0.56	0.08	53	0.7	10	22	0.1	46	AS7-5575a
M-07-43	G37683	68	70	0.27	0.09	98	1.1	10	60	0.1	107	AS7-5575a
M-07-43	G37684	70	72	0.38	0.14	74	1.7	10	34	0.1	119	AS7-5575a
M-07-43	G37685	72	74	0.37	0.19	34	1.5	10	40	0.1	251	AS7-5575a
M-07-43	G37686	74	76	0.88	0.10	46	1.9	20	114	0.1	541	AS7-5575a
M-07-43	G37687	76	78	0.82	0.12	32	1.4	15	30	0.1	86	AS7-5575a
M-07-43	G37688	78	80	0.40	0.18	42	1.5	15	30	0.1	99	AS7-5575a
M-07-43	G37689	80	82	0.41	0.19	47	1.4	20	26	0.1	54	AS7-5575a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-43	G37690	82	84	0.27	0.15	150	1.4	55	46	10	123	AS7-5575a
M-07-43	G37691	84	86	0.27	0.12	48	1.5	80	54	15	144	AS7-5577a
M-07-43	G37692	86	88	0.21	0.05	60	0.7	20	84	0.1	179	AS7-5577a
M-07-43	G37693	88	90	0.45	0.12	47	0.8	10	54	0.1	89	AS7-5577a
M-07-43	G37694	90	92	0.49	0.15	36	0.8	0.1	40	0.1	87	AS7-5577a
M-07-43	G37695	92	94	0.33	0.11	43	0.9	5	66	0.1	84	AS7-5577a
M-07-43	G37696	94	96	0.28	0.12	32	0.9	0.1	32	0.1	106	AS7-5577a
M-07-43	G37697	96	98	0.33	0.13	34	1	10	28	0.1	25	AS7-5577a
M-07-43	G37698	98	100	0.39	0.11	41	0.7	0.1	22	0.1	16	AS7-5577a
M-07-43	G37699	100	102	0.39	0.13	42	1.1	0.1	24	0.1	32	AS7-5577a
M-07-43	G37700	102	104	0.69	0.21	58	1.5	10	28	0.1	84	AS7-5577a
M-07-43	G37701	104	106	0.41	0.14	33	0.8	0.1	28	0.1	37	AS7-5577a
M-07-43	G37702	106	108	0.48	0.17	61	0.8	10	30	0.1	32	AS7-5577a
M-07-43	G37703	108	110	0.39	0.15	41	0.7	0.1	30	0.1	37	AS7-5577a
M-07-43	G37704	110	112	0.56	0.12	60	0.7	0.1	30	0.1	109	AS7-5577a
M-07-43	G37705	112	114	0.48	0.15	39	1	15	20	0.1	54	AS7-5577a
M-07-43	G37706	114	116	0.22	0.10	56	0.8	10	28	0.1	23	AS7-5577a
M-07-43	G37707	116	118	0.24	0.13	48	1.5	45	34	10	32	AS7-5577a
M-07-43	G37708	118	120	0.29	0.10	60	1.7	80	32	10	67	AS7-5577a
M-07-43	G37709	120	122	0.44	0.17	39	3.4	250	74	65	161	AS7-5577a
M-07-43	G37712	122	124	0.99	0.10	49	0.8	15	28	35	55	AS7-5577a
M-07-43	G37713	124	126	0.29	0.07	46	1	80	50	15	74	AS7-5577a
M-07-43	G37714	126	128	0.24	0.12	53	1.6	200	68	35	107	AS7-5577a
M-07-43	G37715	128	130	0.24	0.16	38	1.5	160	36	10	80	AS7-5577a
M-07-43	G37716	130	132	0.31	0.14	39	2.1	275	86	15	104	AS7-5577a
M-07-43	G37717	132	134	0.46	0.16	112	2.4	380	524	25	179	AS7-5577a
M-07-43	G37718	134	136	0.25	0.10	41	2.6	200	120	30	119	AS7-5577a
M-07-43	G37719	136	138	0.36	0.11	95	1.9	80	26	0.1	54	AS7-5577a
M-07-43	G37720	138	140	0.39	0.12	122	2.1	50	20	5	41	AS7-5577a
M-07-43	G37721	140	142	0.45	0.13	109	0.9	30	18	0.1	77	AS7-5577a
M-07-43	G37722	142	144	0.36	0.09	90	0.7	15	22	0.1	62	AS7-5577a
M-07-43	G37723	144	146	0.40	0.12	66	1	20	18	35	29	AS7-5577a
M-07-43	G37724	146	148	0.39	0.12	76	0.9	15	26	0.1	71	AS7-5577a
M-07-43	G37725	148	150	0.39	0.12	69	1.1	20	22	0.1	29	AS7-5577a
M-07-43	G37726	150	152	0.50	0.17	75	2	95	32	15	127	AS7-5578a
M-07-43	G37727	152	154	0.55	0.16	39	0.7	0.1	18	0.1	51	AS7-5578a
M-07-43	G37728	154	156	0.29	0.13	60	0.8	10	30	0.1	56	AS7-5578a
M-07-43	G37729	156	158	0.25	0.15	596	0.7	10	38	0.1	79	AS7-5578a
M-07-43	G37730	158	160	0.44	0.16	77	1.2	0.1	70	0.1	87	AS7-5578a
M-07-43	G37731	160	162	0.66	0.14	51	1.2	0.1	56	0.1	145	AS7-5578a
M-07-43	G37732	162	164	0.63	0.17	56	1.5	0.1	72	0.1	74	AS7-5578a
M-07-43	G37733	164	166	0.78	0.11	50	1.6	0.1	46	0.1	123	AS7-5578a
M-07-43	G37734	166	168	0.76	0.15	69	2.1	0.1	50	5	130	AS7-5578a
M-07-43	G37735	168	170	0.72	0.11	67	1.6	0.1	80	0.1	75	AS7-5578a
M-07-43	G37736	170	172	0.62	0.13	63	1.8	0.1	58	15	137	AS7-5578a
M-07-43	G37737	172	174	0.79	0.13	67	1.4	0.1	28	0.1	76	AS7-5578a
M-07-43	G37738	174	176	0.79	0.12	130	1.1	0.1	50	10	176	AS7-5578a
M-07-43	G37739	176	178	0.61	0.09	80	1	0.1	34	5	127	AS7-5578a
M-07-43	G37741	178	180	0.34	0.07	60	0.8	0.1	32	0.1	90	AS7-5578a
M-07-43	G37742	180	182	0.43	0.08	81	1.1	0.1	44	5	127	AS7-5578a
M-07-43	G37743	182	184	0.42	0.07	51	0.9	0.1	42	25	190	AS7-5578a
M-07-43	G37744	184	186	0.49	0.10	53	1.1	0.1	64	0.1	126	AS7-5578a
M-07-43	G37745	186	188	0.47	0.08	69	2.1	0.1	60	15	157	AS7-5578a
M-07-43	G37746	188	190	0.54	0.09	71	1.3	0.1	32	0.1	67	AS7-5578a
M-07-43	G37749	190	192	0.77	0.10	128	1	0.1	46	5	90	AS7-5578a
M-07-43	G37750	192	194	0.67	0.10	213	1.5	0.1	66	5	124	AS7-5578a
M-07-43	G37751	194	196	0.64	0.10	73	2	0.1	58	0.1	57	AS7-5578a
M-07-43	G37752	196	198	0.87	0.12	80	2.7	0.1	58	10	82	AS7-5578a
M-07-43	G37753	198	200	0.39	0.07	65	1.4	5	44	5	117	AS7-5578a
M-07-43	G37754	200	202	0.83	0.10	63	1.7	0.1	54	15	134	AS7-5578a
M-07-43	G37755	202	204	0.44	0.08	52	1.3	0.1	66	15	140	AS7-5578a
M-07-43	G37756	204	206	0.57	0.09	194	1.7	0.1	80	15	102	AS7-5578a
M-07-43	G37757	206	208	0.41	0.07	148	1.1	10	56	10	103	AS7-5578a
M-07-43	G37758	208	210	0.54	0.09	150	1.3	5	60	130	156	AS7-5578a
M-07-43	G37759	210	212	0.54	0.11	65	1.4	5	80	5	98	AS7-5578a
M-07-43	G37761	212	214	0.42	0.10	505	1.6	15	100	10	104	AS7-5581a
M-07-43	G37762	214	216	0.46	0.09	101	1.6	0.1	106	0.1	83	AS7-5581a
M-07-43	G37763	216	218	0.55	0.08	84	1.1	20	66	20	123	AS7-5581a
M-07-43	G37764	218	220	0.44	0.08	179	1.4	10	56	0.1	76	AS7-5581a
M-07-43	G37765	220	222	0.40	0.06	67	0.9	10	56	15	147	AS7-5581a
M-07-43	G37766	222	224	0.46	0.09	64	1.4	25	66	15	149	AS7-5581a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-43	G37767	224	226	0.34	0.07	74	1.3	30	88	10	141	AS7-5581a
M-07-43	G37768	226	228	0.51	0.09	127	1.4	20	80	10	109	AS7-5581a
M-07-43	G37769	228	230	0.48	0.08	109	1	0.1	74	0.1	93	AS7-5581a
M-07-43	G37771	230	232	0.49	0.11	132	1.6	10	106	15	105	AS7-5581a
M-07-43	G37772	232	234	0.31	0.06	72	0.9	15	58	15	152	AS7-5581a
M-07-43	G37773	234	236	0.36	0.06	115	1	10	70	5	125	AS7-5581a
M-07-43	G37774	236	238	0.30	0.07	84	1.2	20	60	20	176	AS7-5581a
M-07-43	G37775	238	240	0.43	0.09	113	1.2	15	80	0.1	182	AS7-5581a
M-07-43	G37776	240	242	0.39	0.08	72	1.1	30	242	10	296	AS7-5581a
M-07-43	G37777	242	244	0.48	0.08	130	0.9	10	38	10	149	AS7-5581a
M-07-43	G37778	244	246	0.31	0.07	172	1	15	48	0.1	187	AS7-5581a
M-07-43	G37779	246	248	0.31	0.03	101	0.7	15	48	10	189	AS7-5581a
M-07-43	G37780	248	250	0.52	0.03	71	0.8	15	36	0.1	95	AS7-5581a
M-07-43	G37781	250	252	0.31	0.01	83	0.4	10	38	15	163	AS7-5581a
M-07-43	G37782	252	253.5	0.33	0.04	83	0.5	20	44	30	179	AS7-5581a
M-07-43	G37783	253.5	254.85	0.33	0.09	47	1.8	10	60	10	98	AS7-5581a
M-07-43	G37784	254.85	256	0.79	0.23	18	2.4	0.1	50	0.1	90	AS7-5581a
M-07-43	G37785	256	258	0.99	0.27	627	2.7	10	34	0.1	106	AS7-5581a
M-07-43	G37786	258	260	1.16	0.27	607	3	0.1	30	0.1	98	AS7-5581a
M-07-43	G37787	260	262	1.26	0.25	40	2.8	0.1	30	5	132	AS7-5581a
M-07-43	G37788	262	264	0.82	0.19	23	2.7	0.1	34	0.1	83	AS7-5581a
M-07-43	G37789	264	264	0.61	0.11	130	1.7	0.1	34	0.1	73	AS7-5581a
M-07-43	G37791	266	268	0.48	0.10	117	1.4	0.1	34	0.1	68	AS7-5581a
M-07-43	G37792	268	270	0.80	0.10	49	1.1	10	30	0.1	101	AS7-5581a
M-07-43	G37793	270	272	0.62	0.11	38	1.1	5	32	15	107	AS7-5581a
M-07-43	G37794	272	274	0.55	0.14	60	1.8	5	32	0.1	87	AS7-5581a
M-07-43	G37795	274	276	0.55	0.13	42	1.7	0.1	26	0.1	59	AS7-5581a
M-07-43	G37796	276	278	0.99	0.15	19	1.7	0.1	30	15	79	AS7-5583a
M-07-43	G37797	278	280	1.03	0.19	19	1.8	0.1	28	15	64	AS7-5583a
M-07-43	G37798	280	282	0.56	0.14	18	1.1	0.1	22	0.1	35	AS7-5583a
M-07-43	G37799	282	284	0.15	0.06	30	0.8	0.1	20	0.1	26	AS7-5583a
M-07-43	G37800	284	286	0.56	0.08	62	1	0.1	32	15	80	AS7-5583a
M-07-43	G37801	286	288	0.24	0.07	62	0.8	0.1	22	0.1	27	AS7-5583a
M-07-43	G37802	288	290	0.23	0.07	27	0.7	0.1	26	0.1	59	AS7-5583a
M-07-43	G37803	290	292	0.33	0.08	48	0.7	0.1	34	30	99	AS7-5583a
M-07-43	G37804	292	294	0.27	0.05	33	0.6	0.1	24	0.1	52	AS7-5583a
M-07-43	G37805	294	296	0.26	0.04	47	0.7	0.1	24	0.1	24	AS7-5583a
M-07-43	G37807	296	298	0.18	0.05	62	0.6	0.1	22	10	41	AS7-5583a
M-07-43	G37808	298	300	0.12	0.05	26	1	0.1	24	0.1	30	AS7-5583a
M-07-43	G37809	300	302	0.29	0.06	32	0.5	0.1	28	5	56	AS7-5583a
M-07-43	G37810	302	304	0.15	0.05	42	0.5	0.1	24	0.1	46	AS7-5583a
M-07-43	G37811	304	306	0.19	0.05	52	0.4	0.1	32	15	67	AS7-5583a
M-07-43	G37812	306	308	0.27	0.08	44	0.6	0.1	34	10	53	AS7-5583a
M-07-43	G37813	308	310	0.30	0.07	69	0.4	0.1	28	10	49	AS7-5583a
M-07-43	G37814	310	311.4	0.40	0.10	52	0.5	0.1	30	10	47	AS7-5583a
M-07-43	G37815	311.4	312.71	0.44	0.11	28	0.7	0.1	26	15	47	AS7-5583a
M-07-44	G37816	1.3	3	0.36	0.17	39	2.7	30	228	10	122	AS7-5583a
M-07-44	G37817	3	5	0.18	0.09	14	2.6	0.1	210	0.1	67	AS7-5583a
M-07-44	G37818	5	7	0.17	0.09	64	1.8	10	242	10	114	AS7-5583a
M-07-44	G37820	7	9	0.00	0.04	10	2.4	0.1	226	10	86	AS7-5583a
M-07-44	G37821	9	11	0.09	0.04	17	2.5	15	446	10	353	AS7-5583a
M-07-44	G37822	11	13	0.17	0.04	13	4.7	10	840	5	865	AS7-5583a
M-07-44	G37823	13	15	0.10	0.05	13	3.6	15	880	10	775	AS7-5583a
M-07-44	G37824	15	17	0.08	0.05	26	3.7	10	814	15	246	AS7-5583a
M-07-44	G37825	17	19	0.11	0.07	30	3.1	0.1	514	15	119	AS7-5583a
M-07-44	G37827	19	21	0.10	0.13	29	3.5	0.1	458	15	76	AS7-5583a
M-07-44	G37828	21	22.3	0.04	0.04	13	1.6	15	270	25	120	AS7-5583a
M-07-44	G37829	22.3	24	0.05	0.03	57	0.9	15	100	5	63	AS7-5583a
M-07-44	G37830	24	26	0.04	0.07	41	0.9	10	72	0.1	65	AS7-5583a
M-07-44	G37831	26	28	0.04	0.03	26	0.7	25	112	10	214	AS7-5584a
M-07-44	G37832	28	30	0.03	0.04	49	1	15	50	10	44	AS7-5584a
M-07-44	G37833	30	32	0.08	0.03	56	1.3	45	106	5	58	AS7-5584a
M-07-44	G37834	32	34	0.16	0.08	477	5.3	35	1006	15	1065	AS7-5584a
M-07-44	G37835	34	36	0.11	0.14	50	3.8	35	136	0.1	69	AS7-5584a
M-07-44	G37836	36	38	0.13	0.16	35	4.6	50	162	5	47	AS7-5584a
M-07-44	G37838	38	40	0.03	0.13	25	3.1	15	248	5	199	AS7-5584a
M-07-44	G37839	40	42	0.00	0.12	13	2.4	15	102	10	150	AS7-5584a
M-07-44	G37840	42	43.4	0.11	0.10	22	3.4	5	454	0.1	165	AS7-5584a
M-07-44	G37841	43.4	45	0.06	0.01	25	0.9	0.1	62	15	128	AS7-5584a
M-07-44	G37842	45	47	0.15	0.01	40	1.6	25	120	0.1	167	AS7-5584a
M-07-44	G37843	47	49	0.20	0.01	99	0.6	15	50	10	92	AS7-5584a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-44	G37844	49	51	0.31	0.01	50	1	15	134	15	290	AS7-5584a
M-07-44	G37845	51	52.3	0.27	0.00	32	0.8	10	48	30	94	AS7-5584a
M-07-44	G37846	52.3	53.55	0.16	0.00	27	0.8	25	40	20	94	AS7-5584a
M-07-44	G37847	53.55	55.45	0.10	0.02	6	3	40	40	75	96	AS7-5584a
M-07-44	G37848	55.45	57	0.28	0.02	4	4.3	20	60	65	86	AS7-5584a
M-07-44	G37849	57	59	0.30	0.08	10	20.7	85	122	345	209	AS7-5584a
M-07-44	G37850	59	61	0.05	0.03	5	1	0.1	34	20	42	AS7-5584a
M-07-44	G37851	61	63	0.14	0.03	38	1.2	20	58	25	60	AS7-5584a
M-07-44	G37852	63	65	0.11	0.04	11	2.8	30	32	70	44	AS7-5584a
M-07-44	G37854	65	67	0.11	0.03	56	0.8	0.1	32	15	42	AS7-5584a
M-07-44	G37855	67	69	0.11	0.06	23	2.1	20	28	20	61	AS7-5584a
M-07-44	G37856	69	70.4	0.06	0.05	33	8	85	48	85	100	AS7-5584a
M-07-44	G37857	70.4	71.7	0.06	0.04	27	3.3	40	40	25	72	AS7-5584a
M-07-44	G37858	71.7	73	0.16	0.04	9	1.3	10	22	5	23	AS7-5584a
M-07-44	G37859	73	75	0.57	0.07	48	2.2	0.1	30	15	41	AS7-5584a
M-07-44	G37860	75	77	0.34	0.07	48	1.4	0.1	32	15	30	AS7-5584a
M-07-44	G37861	77	79	0.46	0.06	168	1.2	15	34	0.1	33	AS7-5584a
M-07-44	G37862	79	81	0.33	0.04	16	1.3	10	32	15	65	AS7-5584a
M-07-44	G37863	81	83	0.09	0.06	83	1.6	0.1	48	15	80	AS7-5584a
M-07-44	G37864	83	85	0.09	0.07	24	2.1	15	46	20	67	AS7-5584a
M-07-44	G37865	85	87	0.08	0.05	26	1	15	32	10	45	AS7-5584a
M-07-44	G37866	87	89	0.10	0.12	79	12.9	130	142	345	224	AS7-5585a
M-07-44	G37867	89	91	0.06	0.06	29	1.1	10	40	35	64	AS7-5585a
M-07-44	G37868	91	93	0.10	0.06	68	0.7	5	30	10	52	AS7-5585a
M-07-44	G37869	93	95	0.23	0.05	177	2.8	35	48	45	62	AS7-5585a
M-07-44	G37870	95	97	0.18	0.06	31	1.1	15	36	15	85	AS7-5585a
M-07-44	G37871	97	99	0.27	0.09	96	5.2	40	30	45	53	AS7-5585a
M-07-44	G37872	99	101	0.17	0.07	56	1.4	10	38	5	54	AS7-5585a
M-07-44	G37873	101	103	0.14	0.08	54	1.8	0.1	62	20	212	AS7-5585a
M-07-44	G37874	103	105	0.23	0.10	31	2.7	0.1	68	10	74	AS7-5585a
M-07-44	G37875	105	107	0.16	0.08	25	1.1	0.1	54	5	49	AS7-5585a
M-07-44	G37877	107	109	0.29	0.09	115	3.7	10	48	15	76	AS7-5585a
M-07-44	G37878	109	111	0.21	0.09	53	2.4	10	34	25	52	AS7-5585a
M-07-44	G37879	111	113	0.28	0.10	44	19.5	105	184	290	389	AS7-5585a
M-07-44	G37881	113	115	0.25	0.08	63	6.9	20	76	30	86	AS7-5585a
M-07-44	G37882	115	117	0.24	0.10	97	6.4	15	112	10	149	AS7-5585a
M-07-44	G37883	117	119	0.27	0.04	39	1.9	15	46	5	85	AS7-5585a
M-07-44	G37884	119	121	0.14	0.05	29	2.3	10	44	10	82	AS7-5585a
M-07-44	G37885	121	123	0.26	0.09	74	4.6	10	52	20	93	AS7-5585a
M-07-44	G37887	123	124.5	0.21	0.05	47	2.6	15	36	10	106	AS7-5585a
M-07-44	G37888	124.5	126	0.35	0.12	71	9.1	25	128	15	135	AS7-5585a
M-07-44	G37889	126	128	0.47	0.17	79	9.3	115	68	155	90	AS7-5585a
M-07-44	G37890	128	130	0.21	0.08	57	6.3	85	80	120	97	AS7-5585a
M-07-44	G37891	130	132	0.50	0.06	80	14.3	120	92	165	82	AS7-5585a
M-07-44	G37892	132	134	0.20	0.06	45	1.5	20	36	10	114	AS7-5585a
M-07-44	G37893	134	136	0.22	0.09	47	1.7	10	78	0.1	151	AS7-5585a
M-07-44	G37894	136	138	1.68	0.09	47	4.5	40	130	35	189	AS7-5585a
M-07-44	G37895	138	140	0.52	0.08	66	5.1	75	64	60	88	AS7-5585a
M-07-44	G37896	140	142	0.41	0.12	73	19.5	245	88	430	201	AS7-5585a
M-07-44	G37897	142	144	1.26	0.10	89	8.5	75	72	95	90	AS7-5585a
M-07-44	G37898	144	146	0.27	0.07	81	1.7	15	30	10	85	AS7-5585a
M-07-44	G37899	146	148	0.46	0.09	45	3.1	30	40	30	121	AS7-5585a
M-07-44	G37900	148	150	0.40	0.09	88	1.7	25	40	10	104	AS7-5585a
M-07-44	G37901	150	152	0.33	0.08	41	2.1	20	90	0.1	403	AS7-5586a
M-07-44	G37902	152	154	0.33	0.06	50	1.6	15	68	15	116	AS7-5586a
M-07-44	G37903	154	156	0.24	0.06	52	1.1	0.1	48	10	58	AS7-5586a
M-07-44	G37904	156	158	0.33	0.08	73	1.2	0.1	58	15	55	AS7-5586a
M-07-44	G37905	158	160	0.59	0.05	88	2.4	10	106	15	87	AS7-5586a
M-07-44	G37907	160	162	0.60	0.07	61	2.2	0.1	80	5	88	AS7-5586a
M-07-44	G37908	162	164	0.34	0.06	172	2.2	0.1	56	0.1	80	AS7-5586a
M-07-44	G37909	164	166	0.56	0.06	73	1.9	10	62	10	96	AS7-5586a
M-07-44	G37910	166	167	1.06	0.07	66	2.7	30	64	10	103	AS7-5586a
M-07-44	G37911	167	168.55	0.41	0.04	69	1.5	15	46	15	162	AS7-5586a
M-07-44	G37912	168.55	170	0.43	0.09	49	1.4	25	48	10	197	AS7-5586a
M-07-44	G37913	170	172	0.37	0.09	69	1.8	15	54	5	113	AS7-5586a
M-07-44	G37914	172	174	0.31	0.09	40	1.7	10	58	0.1	118	AS7-5586a
M-07-44	G37915	174	176	0.45	0.10	49	1.2	0.1	64	20	153	AS7-5586a
M-07-44	G37916	176	178	0.56	0.08	113	1.1	0.1	88	10	141	AS7-5586a
M-07-44	G37917	178	180	0.63	0.10	78	1.1	0.1	68	15	163	AS7-5586a
M-07-44	G37918	180	182	0.40	0.11	75	1.1	0.1	60	15	100	AS7-5586a
M-07-44	G37919	182	184	0.32	0.08	101	1.2	0.1	78	0.1	78	AS7-5586a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-44	G37920	184	186	0.30	0.08	50	1	5	74	15	121	AS7-5586a
M-07-44	G37921	186	188	0.66	0.10	91	0.8	0.1	58	15	109	AS7-5586a
M-07-44	G37922	188	190	0.44	0.06	83	0.9	0.1	60	0.1	86	AS7-5586a
M-07-44	G37923	190	192	0.33	0.08	53	1.3	0.1	78	0.1	106	AS7-5586a
M-07-44	G37924	192	194	0.17	0.10	51	1.2	5	42	0.1	64	AS7-5586a
M-07-44	G37925	194	196	0.83	0.10	59	1.3	0.1	0.1	0.1	160	AS7-5586a
M-07-44	G37926	196	198	0.77	0.12	179	1.2	0.1	32	95	76	AS7-5586a
M-07-44	G37927	198	200	0.54	0.11	51	1.4	0.1	34	0.1	45	AS7-5586a
M-07-44	G37929	200	202	0.30	0.11	141	0.9	10	28	0.1	43	AS7-5586a
M-07-44	G37930	202	204	0.45	0.08	66	1.4	5	34	0.1	61	AS7-5586a
M-07-44	G37931	204	206	0.49	0.08	36	1.2	5	54	0.1	72	AS7-5586a
M-07-44	G37933	206	208	0.44	0.07	43	1.1	0.1	66	0.1	143	AS7-5586a
M-07-44	G37934	208	210	0.31	0.06	20	0.9	10	60	0.1	94	AS7-5586a
M-07-44	G37935	210	212	0.26	0.05	40	1	0.1	74	0.1	233	AS7-5586a
M-07-44	G37936	212	214	0.20	0.05	30	0.8	0.1	58	0.1	193	AS7-5587a
M-07-44	G37937	214	216	0.18	0.08	69	1.1	0.1	70	0.1	183	AS7-5587a
M-07-44	G37938	216	218	0.46	0.06	41	1.1	0.1	46	0.1	90	AS7-5587a
M-07-44	G37939	218	220	0.52	0.06	30	1	0.1	36	0.1	83	AS7-5587a
M-07-44	G37940	220	222	0.37	0.06	32	0.8	0.1	46	0.1	162	AS7-5587a
M-07-44	G37941	222	224	0.25	0.05	44	1.1	0.1	56	45	107	AS7-5587a
M-07-44	G37942	224	226	0.51	0.06	25	1	0.1	28	0.1	94	AS7-5587a
M-07-44	G37943	226	228	0.27	0.06	23	1	0.1	36	0.1	206	AS7-5587a
M-07-44	G37944	228	230	0.59	0.05	72	1.4	0.1	76	0.1	404	AS7-5587a
M-07-44	G37945	230	232	0.58	0.05	28	1	0.1	52	0.1	157	AS7-5587a
M-07-44	G37948	232	234	0.41	0.04	166	1.1	0.1	46	0.1	207	AS7-5587a
M-07-44	G37949	234	236	0.33	0.05	14	1	0.1	30	0.1	67	AS7-5587a
M-07-44	G37950	236	238	0.31	0.05	61	1.1	0.1	38	0.1	183	AS7-5587a
M-07-44	G37951	238	240	0.51	0.06	40	1	0.1	28	0.1	198	AS7-5587a
M-07-44	G37952	240	242	0.63	0.06	35	1.1	0.1	26	0.1	72	AS7-5587a
M-07-44	G37953	242	244	0.38	0.04	44	0.8	0.1	22	0.1	35	AS7-5587a
M-07-44	G37954	244	245.8	0.44	0.04	40	1.1	0.1	22	0.1	120	AS7-5587a
M-07-44	G37955	245.8	247	0.45	0.07	97	1.4	0.1	26	0.1	423	AS7-5587a
M-07-44	G37956	247	249	0.58	0.06	121	1.6	0.1	24	0.1	830	AS7-5587a
M-07-44	G37957	249	251	0.91	0.10	112	2.6	0.1	32	0.1	208	AS7-5587a
M-07-44	G37958	251	253	0.87	0.09	90	2.5	0.1	48	0.1	228	AS7-5587a
M-07-44	G37960	253	255	1.06	0.07	64	2.5	0.1	36	0.1	190	AS7-5587a
M-07-44	G37961	255	257	1.42	0.07	78	2.3	0.1	22	0.1	304	AS7-5587a
M-07-44	G37962	257	259	0.78	0.06	92	1.9	5	24	0.1	380	AS7-5587a
M-07-44	G37963	259	261	1.23	0.11	114	2.7	25	46	0.1	212	AS7-5587a
M-07-44	G37964	261	263	0.68	0.09	102	1.9	5	58	5	346	AS7-5587a
M-07-44	G37965	263	265	0.77	0.09	144	2.2	15	52	0.1	201	AS7-5587a
M-07-44	G37966	265	267	1.10	0.11	121	2.8	10	52	0.1	240	AS7-5587a
M-07-44	G37967	267	268.5	0.74	0.09	125	1.8	25	60	15	516	AS7-5587a
M-07-44	G37968	268.5	269.9	0.43	0.07	74	2.3	10	228	15	337	AS7-5587a
M-07-44	G37969	269.9	272	0.64	0.07	62	2	0.1	96	0.1	305	AS7-5587a
M-07-44	G37970	272	274	0.47	0.07	58	1.4	15	92	15	345	AS7-5587a
M-07-44	G37971	274	276	0.62	0.09	98	1.5	35	136	0.1	344	AS7-5589a
M-07-44	G37972	276	278	0.51	0.10	62	1.9	35	166	0.1	418	AS7-5589a
M-07-44	G37973	278	280	0.53	0.10	72	1.8	30	94	0.1	347	AS7-5589a
M-07-44	G37974	280	282	0.88	0.12	62	2.3	35	88	0.1	363	AS7-5589a
M-07-44	G37975	282	284	0.55	0.07	62	1.9	30	54	0.1	306	AS7-5589a
M-07-44	G37976	284	285.6	0.54	0.09	71	3.7	30	34	0.1	401	AS7-5589a
M-07-44	G37977	285.6	287	0.67	0.15	97	4.8	40	166	0.1	224	AS7-5589a
M-07-44	G37978	287	289	0.51	0.08	36	1.7	30	46	0.1	207	AS7-5589a
M-07-44	G37979	289	291	0.46	0.08	46	1.7	30	118	0.1	229	AS7-5589a
M-07-44	G37980	291	293	0.25	0.05	50	1	15	44	0.1	172	AS7-5589a
M-07-44	G37981	293	295	0.29	0.05	31	0.8	15	36	0.1	184	AS7-5589a
M-07-44	G37983	295	297	0.46	0.08	23	1.4	15	44	0.1	223	AS7-5589a
M-07-44	G37984	297	299	0.44	0.06	23	1.6	20	98	0.1	234	AS7-5589a
M-07-44	G37985	299	301	0.35	0.06	42	1.3	20	64	0.1	293	AS7-5589a
M-07-44	G37986	301	303	0.36	0.06	29	1.1	20	60	0.1	163	AS7-5589a
M-07-44	G37987	303	305	0.41	0.07	39	1	15	36	0.1	172	AS7-5589a
M-07-44	G37988	305	307	0.37	0.07	44	1.1	15	58	0.1	229	AS7-5589a
M-07-44	G37990	307	309	0.40	0.05	57	1.1	15	48	0.1	213	AS7-5589a
M-07-44	G37991	309	311	0.43	0.07	60	1.2	15	70	0.1	232	AS7-5589a
M-07-44	G37992	311	312.6	0.37	0.05	35	0.7	15	32	0.1	240	AS7-5589a
M-07-44	G37993	312.6	314.2	0.56	0.07	42	1.4	30	102	0.1	199	AS7-5589a
M-07-44	G37994	314.2	316	0.47	0.07	52	1.1	25	40	0.1	292	AS7-5589a
M-07-44	G37995	316	318	2.25	0.05	50	0.9	25	62	0.1	219	AS7-5589a
M-07-44	G37996	318	320	0.39	0.05	63	1.2	25	110	0.1	222	AS7-5589a
M-07-44	G37997	320	322	0.94	0.07	41	2	40	114	0.1	190	AS7-5589a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-44	G37998	322	324	0.53	0.05	70	0.9	20	44	0.1	216	AS7-5589a
M-07-44	G37999	324	326	0.45	0.06	51	0.6	15	34	0.1	190	AS7-5589a
M-07-44	G38000	326	328	0.33	0.06	51	0.9	15	32	0.1	166	AS7-5589a
M-07-44	X09001	328	330	0.52	0.05	120	0.9	15	34	0.1	225	AS7-5589a
M-07-44	X09002	330	332	0.32	0.04	37		15	37	0.1	202	AS7-5590a
M-07-44	X09003	332	334	0.51	0.06	59		15	29	0.1	216	AS7-5590a
M-07-44	X09004	334	336	0.34	0.04	34		20	22	0.1	211	AS7-5590a
M-07-44	X09005	336	338	0.53	0.06	41		30	104	0.1	205	AS7-5590a
M-07-44	X09006	338	340	0.69	0.07	97		15	82	0.1	370	AS7-5590a
M-07-44	X09007	340	342	0.61	0.09	95		25	395	0.1	723	AS7-5590a
M-07-44	X09008	342	344	0.70	0.05	77		105	93	65	355	AS7-5590a
M-07-44	X09009	344	346	0.41	0.05	71		30	26	0.1	202	AS7-5590a
M-07-44	X09010	346	348	3.70	0.05	127		20	78	0.1	219	AS7-5590a
M-07-44	X09011	348	350	0.48	0.04	81		20	27	0.1	197	AS7-5590a
M-07-44	X09012	350	352	0.60	0.05	95		20	38	0.1	191	AS7-5590a
M-07-44	X09013	352	354	0.52	0.06	155		15	34	0.1	215	AS7-5590a
M-07-44	X09014	354	356	0.55	0.06	88		20	34	0.1	271	AS7-5590a
M-07-44	X09015	356	358	0.50	0.05	90		15	32	0.1	280	AS7-5590a
M-07-44	X09016	358	360	0.43	0.05	79		25	61	10	164	AS7-5590a
M-07-44	X09017	360	362	0.90	0.11	96		20	75	0.1	241	AS7-5590a
M-07-44	X09018	362	364	0.55	0.08	111		20	26	0.1	312	AS7-5590a
M-07-44	X09019	364	366	0.36	0.05	80		15	66	0.1	233	AS7-5590a
M-07-44	X09020	366	368	0.44	0.04	132		15	32	0.1	203	AS7-5590a
M-07-44	X09021	368	370	0.66	0.05	172		25	51	0.1	235	AS7-5590a
M-07-44	X09022	370	372	0.81	0.04	109		35	35	5	372	AS7-5590a
M-07-44	X09024	372	374	0.61	0.04	79		20	35	0.1	247	AS7-5590a
M-07-44	X09025	374	376	0.40	0.06	77		20	51	0.1	227	AS7-5590a
M-07-44	X09026	376	378	0.63	0.07	174		15	26	0.1	242	AS7-5590a
M-07-44	X09027	378	380	0.48	0.04	102		20	26	0.1	212	AS7-5590a
M-07-44	X09028	380	382	0.65	0.06	72		30	22	0.1	243	AS7-5590a
M-07-44	X09029	382	384	0.67	0.05	77		25	69	0.1	252	AS7-5590a
M-07-44	X09030	384	386	0.49	0.05	109		20	22	0.1	245	AS7-5590a
M-07-44	X09031	386	388	0.46	0.05	124		25	27	0.1	222	AS7-5590a
M-07-44	X09032	388	390	0.56	0.05	87		15	26	0.1	207	AS7-5590a
M-07-44	X09034	390	392	0.40	0.05	109		30	34	0.1	207	AS7-5590a
M-07-44	X09035	392	394	0.66	0.06	118		20	38	0.1	225	AS7-5590a
M-07-44	X09036	394	396	0.56	0.08	168		20	27	0.1	184	AS7-5590a
M-07-44	X09037	396	398	0.41	0.05	129	0.6	25	28	0.1	109	AS7-5592a
M-07-44	X09038	398	400	0.77	0.09	147	1.5	20	20	0.1	140	AS7-5592a
M-07-44	X09039	400	402	0.91	0.14	60	41.3	50	44	95	145	AS7-5592a
M-07-44	X09040	402	404	0.26	0.04	93	2.6	15	30	0.1	158	AS7-5592a
M-07-44	X09041	404	406	0.28	0.04	71	1.2	20	22	0.1	144	AS7-5592a
M-07-44	X09042	406	408	0.72	0.08	130	1.5	20	16	0.1	158	AS7-5592a
M-07-44	X09043	408	410	0.71	0.11	65	3.4	25	56	5	87	AS7-5592a
M-07-44	X09044	410	412	0.71	0.08	84	1.3	20	20	0.1	158	AS7-5592a
M-07-44	X09045	412	414	0.51	0.08	58	1.9	20	52	0.1	169	AS7-5592a
M-07-44	X09046	414	416.25	0.49	0.08	86	2.5	25	38	0.1	217	AS7-5592a
M-07-44	X09047	416.25	418	0.47	0.06	64	2.2	20	30	5	159	AS7-5592a
M-07-44	X09048	418	420	0.42	0.09	146	1.8	15	54	0.1	92	AS7-5592a
M-07-44	X09049	420	422	0.45	0.06	81	1.5	20	24	0.1	120	AS7-5592a
M-07-44	X09050	422	424	0.70	0.11	62	1.3	25	26	0.1	199	AS7-5592a
M-07-44	X09051	424	426	0.66	0.09	150	1.2	15	32	0.1	195	AS7-5592a
M-07-44	X09052	426	428	0.68	0.09	170	0.9	15	20	0.1	109	AS7-5592a
M-07-44	X09054	428	430	0.52	0.09	135	1.1	10	26	0.1	73	AS7-5592a
M-07-44	X09055	430	432	0.42	0.05	94	0.8	10	14	0.1	106	AS7-5592a
M-07-44	X09056	432	434	0.52	0.10	102	1.3	10	50	0.1	59	AS7-5592a
M-07-44	X09057	434	436	0.56	0.09	65	2.3	15	28	0.1	46	AS7-5592a
M-07-44	X09058	436	438	0.62	0.10	125	7.2	25	54	10	53	AS7-5592a
M-07-44	X09059	438	440	0.40	0.08	129	1.3	10	44	0.1	89	AS7-5592a
M-07-44	X09060	440	442.5	0.51	0.09	106	1.2	10	64	0.1	128	AS7-5592a
M-07-44	X09061	442.5	444	0.48	0.08	56	0.9	10	76	0.1	101	AS7-5592a
M-07-44	X09062	444	446	0.42	0.06	188	1.2	10	126	0.1	66	AS7-5592a
M-07-44	X09064	446	448	0.34	0.09	138	2.3	10	160	0.1	41	AS7-5592a
M-07-44	X09065	448	450	0.45	0.06	202	3.5	15	84	10	65	AS7-5592a
M-07-44	X09066	450	452	0.08	0.01	39	0.8	0.1	74	0.1	33	AS7-5592a
M-07-44	X09067	452	454	0.43	0.08	185	1.6	10	48	0.1	85	AS7-5592a
M-07-44	X09068	454	456	0.50	0.06	116	1.1	10	38	0.1	116	AS7-5592a
M-07-44	X09069	456	458	0.19	0.04	82	0.8	10	46	0.1	126	AS7-5592a
M-07-44	X09070	458	460	0.31	0.05	111	0.8	10	36	0.1	174	AS7-5592a
M-07-44	X09071	460	462	0.39	0.06	100	1	10	26	0.1	106	AS7-5592a
M-07-44	X09072	462	464	0.52	0.10	84	1.6	0.1	92	10	235	AS7-5594a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-44	X09073	464	466	0.31	0.07	84	0.8	0.1	34	0.1	83	AS7-5594a
M-07-44	X09074	466	468	0.41	0.09	69	1	0.1	34	25	138	AS7-5594a
M-07-44	X09075	468	470	0.52	0.15	112	1.3	0.1	44	5	93	AS7-5594a
M-07-44	X09076	470	472	0.50	0.08	75	1.1	10	32	10	137	AS7-5594a
M-07-44	X09077	472	474	0.57	0.11	133	1.2	10	42	10	130	AS7-5594a
M-07-44	X09078	474	476	0.58	0.09	84	1	0.1	32	5	129	AS7-5594a
M-07-44	X09079	476	478	0.69	0.10	122	1.2	10	32	5	146	AS7-5594a
M-07-44	X09080	478	480	0.60	0.11	114	1.3	0.1	48	10	170	AS7-5594a
M-07-44	X09081	480	482	0.52	0.10	89	1.2	0.1	44	0.1	129	AS7-5594a
M-07-44	X09082	482	483.3	0.69	0.13	130	0.9	0.1	32	25	250	AS7-5594a
M-07-44	X09083	483.3	485	0.76	0.16	115	4.2	0.1	144	0.1	218	AS7-5594a
M-07-44	X09084	485	487	0.76	0.12	116	1.1	15	44	0.1	208	AS7-5594a
M-07-44	X09085	487	489	0.41	0.07	123	0.8	5	38	15	219	AS7-5594a
M-07-44	X09086	489	491	0.33	0.07	129	1.1	0.1	76	10	136	AS7-5594a
M-07-44	X09088	491	493	0.62	0.09	78	0.9	25	54	10	159	AS7-5594a
M-07-44	X09089	493	495	0.67	0.10	99	1.1	20	50	20	269	AS7-5594a
M-07-44	X09090	495	497	0.77	0.11	132	2.7	15	64	5	154	AS7-5594a
M-07-44	X09091	497	499	0.95	0.17	189	2.1	10	60	5	164	AS7-5594a
M-07-44	X09092	499	500.7	0.72	0.13	161	1.8	20	64	25	230	AS7-5594a
M-07-44	X09093	500.7	502	0.66	0.11	72	1.6	15	40	30	155	AS7-5594a
M-07-44	X09094	502	504	0.43	0.12	73	4.2	60	88	45	156	AS7-5594a
M-07-44	X09095	504	506	0.53	0.13	93	3.3	30	206	20	368	AS7-5594a
M-07-44	X09096	506	508	0.28	0.19	179	3.5	40	34	30	41	AS7-5594a
M-07-44	X09098	508	510	0.21	0.14	154	5	55	32	50	47	AS7-5594a
M-07-44	X09099	510	512	0.37	0.16	156	1	25	24	15	42	AS7-5594a
M-07-44	X09100	512	514	1.11	0.13	197	0.8	0.1	28	15	54	AS7-5594a
M-07-44	X09101	514	516	0.27	0.14	113	1.1	70	64	5	42	AS7-5594a
M-07-44	X09102	516	518	0.28	0.13	167	0.8	110	38	15	74	AS7-5594a
M-07-44	X09103	518	520	0.39	0.13	171	0.9	60	54	10	82	AS7-5594a
M-07-44	X09104	520	522	0.60	0.10	137	0.6	15	42	10	68	AS7-5594a
M-07-44	X09105	522	524	0.76	0.14	74	1.1	5	56	0.1	46	AS7-5594a
M-07-44	X09106	524	526	0.79	0.14	108	1.5	15	62	10	157	AS7-5594a
M-07-44	X09107	526	528	0.91	0.12	124	0.9	5	46	0.1	135	AS7-5596a
M-07-44	X09108	528	530	0.64	0.12	107	0.9	15	52	10	88	AS7-5596a
M-07-44	X09109	530	532	0.72	0.13	106	1.2	0.1	110	10	170	AS7-5596a
M-07-44	X09110	532	534	0.55	0.08	112	0.4	20	42	10	154	AS7-5596a
M-07-44	X09111	534	535.2	0.78	0.09	249	0.7	15	56	0.1	99	AS7-5596a
M-07-44	X09112	535.2	537	0.58	0.08	174	0.5	10	38	10	97	AS7-5596a
M-07-44	X09113	537	539	0.49	0.09	87	0.4	5	40	0.1	100	AS7-5596a
M-07-44	X09114	539	541	0.53	0.08	85	0.4	20	28	15	81	AS7-5596a
M-07-44	X09115	541	543	0.39	0.09	112	0.7	15	332	0.1	66	AS7-5596a
M-07-44	X09116	543	545	0.46	0.08	232	1.4	55	62	10	87	AS7-5596a
M-07-44	X09117	545	547	0.55	0.08	173	2.1	15	42	0.1	115	AS7-5596a
M-07-44	X09118	547	549	0.52	0.09	132	12.9	30	116	10	178	AS7-5596a
M-07-44	X09119	549	551	0.37	0.07	70	2.9	15	38	0.1	117	AS7-5596a
M-07-44	X09120	551	553	0.51	0.10	226	5.8	105	168	30	129	AS7-5596a
M-07-44	X09121	553	555	0.25	0.04	87	3	55	164	25	97	AS7-5596a
M-07-44	X09122	555	557	0.41	0.09	86	2.4	15	134	15	136	AS7-5596a
M-07-44	X09124	557	559	0.46	0.09	164	1.3	20	78	30	204	AS7-5596a
M-07-44	X09125	559	561	0.34	0.07	125	0.5	20	72	10	125	AS7-5596a
M-07-44	X09126	561	563	0.59	0.08	89	0.7	10	100	20	144	AS7-5596a
M-07-44	X09127	563	565	0.40	0.06	51	0.5	15	68	15	156	AS7-5596a
M-07-44	X09128	565	567	0.38	0.05	86	0.3	15	56	5	95	AS7-5596a
M-07-44	X09129	567	569	0.36	0.07	140	0.5	20	104	20	161	AS7-5596a
M-07-44	X09130	569	571	0.26	0.05	166	0.4	20	70	0.1	128	AS7-5596a
M-07-44	X09131	571	573	0.38	0.05	95	0.9	30	68	5	246	AS7-5596a
M-07-44	X09132	573	575	0.39	0.06	1724	1	40	100	5	192	AS7-5596a
M-07-44	X09133	575	577	0.48	0.05	196	0.7	30	84	10	203	AS7-5596a
M-07-44	X09134	577	579	0.46	0.06	126	0.9	70	110	10	176	AS7-5596a
M-07-44	X09135	579	581	0.49	0.07	91	1.2	115	188	35	204	AS7-5596a
M-07-44	X09136	581	583	0.27	0.06	104	0.7	15	136	0.1	170	AS7-5596a
M-07-44	X09137	583	585	0.38	0.06	139	0.9	5	68	0.1	119	AS7-5596a
M-07-44	X09138	585	587	0.40	0.07	101	0.8	0.1	70	0.1	378	AS7-5596a
M-07-44	X09139	587	588.9	0.37	0.04	88	0.6	0.1	48	0.1	170	AS7-5596a
M-07-44	X09140	588.9	591	0.44	0.05	88	0.8	10	70	0.1	176	AS7-5596a
M-07-44	X09141	591	593	0.46	0.05	95	0.4	0.1	20	0.1	39	AS7-5596a
M-07-44	X09143	593	595	0.35	0.05	100	1.4	0.1	38	0.1	243	AS7-5598a
M-07-44	X09144	595	597	0.34	0.06	97	1	10	24	0.1	85	AS7-5598a
M-07-44	X09145	597	599	0.40	0.07	89	1.1	5	24	0.1	97	AS7-5598a
M-07-44	X09146	599	601	0.39	0.05	120	2.9	135	102	40	145	AS7-5598a
M-07-44	X09147	601	603	0.21	0.04	106	1.5	105	108	25	91	AS7-5598a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-44	X09148	603	605	0.31	0.04	80	0.8	15	76	0.1	75	AS7-5598a
M-07-44	X09149	605	607	0.31	0.03	80	1	20	68	0.1	36	AS7-5598a
M-07-44	X09150	607	609	0.36	0.03	94	2.1	15	478	0.1	3834	AS7-5598a
M-07-44	X09151	609	611	0.44	0.05	75	1.1	10	64	0.1	86	AS7-5598a
M-07-44	X09152	611	613	0.37	0.04	80	0.9	10	32	0.1	39	AS7-5598a
M-07-44	X09153	613	614.4	0.47	0.05	47	0.5	20	20	0.1	40	AS7-5598a
M-07-44	X09154	614.4	616	0.40	0.04	143	0.9	15	36	0.1	51	AS7-5598a
M-07-44	X09155	616	618	0.33	0.04	201	0.7	0.1	46	0.1	43	AS7-5598a
M-07-44	X09156	618	620	0.34	0.03	51	0.7	15	34	0.1	32	AS7-5598a
M-07-44	X09157	620	622	0.58	0.05	79	0.8	20	26	0.1	24	AS7-5598a
M-07-44	X09158	622	624	0.58	0.05	88	0.6	15	24	0.1	25	AS7-5598a
M-07-44	X09160	624	626	0.54	0.03	62	0.5	5	20	0.1	25	AS7-5598a
M-07-44	X09161	626	628	0.54	0.04	66	0.7	0.1	22	0.1	21	AS7-5598a
M-07-44	X09162	628	630	0.39	0.03	66	0.5	20	30	0.1	22	AS7-5598a
M-07-44	X09163	630	632	0.52	0.04	219	0.7	15	26	0.1	28	AS7-5598a
M-07-44	X09164	632	634	0.53	0.04	82	0.6	20	24	0.1	28	AS7-5598a
M-07-44	X09166	634	636	0.32	0.03	119	0.5	25	18	0.1	18	AS7-5598a
M-07-44	X09167	636	638	0.39	0.03	65	0.5	20	18	0.1	22	AS7-5598a
M-07-44	X09168	638	640	0.53	0.04	96	0.8	10	18	0.1	23	AS7-5598a
M-07-44	X09169	640	642	0.37	0.04	66	0.6	10	22	0.1	43	AS7-5598a
M-07-44	X09170	642	644	0.38	0.04	58	0.6	15	18	0.1	30	AS7-5598a
M-07-44	X09171	644	646.14	0.51	0.05	73	0.5	10	20	0.1	30	AS7-5598a
M-07-45	G35555	4.57	6	0.43	0.08	59	4.1	15	170	0.1	346	AS7-5597a
M-07-45	G35556	6	8	0.64	0.12	86	2.1	15	76	0.1	241	AS7-5597a
M-07-45	G35557	8	10	0.41	0.09	62	1.7	15	98	0.1	222	AS7-5597a
M-07-45	G35558	10	12	1.06	0.06	49	1.8	65	58	10	328	AS7-5599a
M-07-45	G35559	12	14	0.58	0.07	200	3.3	80	98	10	193	AS7-5599a
M-07-45	G35560	14	16	0.37	0.09	48	1.7	25	50	0.1	191	AS7-5599a
M-07-45	G35561	16	18	0.31	0.06	47	2.2	30	408	0.1	959	AS7-5599a
M-07-45	G35562	18	20	0.26	0.06	59	1.3	30	78	5	314	AS7-5599a
M-07-45	G35563	20	22	0.32	0.10	53	1.7	45	78	5	160	AS7-5599a
M-07-45	G35564	22	24	0.41	0.12	61	1.9	30	114	5	260	AS7-5599a
M-07-45	G35565	24	26	0.24	0.08	53	1.2	30	74	5	212	AS7-5599a
M-07-45	G35566	26	28	0.36	0.08	53	1	65	36	30	279	AS7-5599a
M-07-45	G35567	28	30	0.34	0.04	100	0.7	40	36	0.1	301	AS7-5599a
M-07-45	G35568	30	32	0.38	0.10	51	1.7	30	162	0.1	141	AS7-5599a
M-07-45	G35569	32	34	0.44	0.05	75	1.1	30	46	0.1	250	AS7-5599a
M-07-45	G35572	34	36	0.55	0.06	76	1.6	30	48	0.1	368	AS7-5599a
M-07-45	G35573	36	38	0.56	0.06	53	1.4	40	88	0.1	307	AS7-5599a
M-07-45	G35574	38	40	0.99	0.11	119	2	40	90	0.1	368	AS7-5599a
M-07-45	G35575	40	42	1.03	0.15	122	1.8	35	92	0.1	357	AS7-5599a
M-07-45	G35576	42	44	0.86	0.11	154	2.4	35	96	0.1	289	AS7-5599a
M-07-45	G35577	44	46	0.49	0.08	91	1.4	40	56	0.1	206	AS7-5599a
M-07-45	G35578	46	48	0.61	0.09	42	1.6	35	64	0.1	250	AS7-5599a
M-07-45	G35579	48	50	0.47	0.08	115	1.3	30	62	0.1	262	AS7-5599a
M-07-45	G35580	50	52	0.40	0.05	94	1.5	25	40	0.1	113	AS7-5599a
M-07-45	G35581	52	53.2	0.45	0.05	115	0.8	25	44	0.1	273	AS7-5599a
M-07-45	G35582	53.2	54.65	0.49	0.12	50	1.7	15	62	0.1	111	AS7-5599a
M-07-45	G35583	54.65	56	0.57	0.08	61	1.2	15	32	0.1	148	AS7-5599a
M-07-45	G35584	56	58	0.36	0.09	13	1.3	15	34	0.1	172	AS7-5599a
M-07-45	G35585	58	60	0.13	0.13	22	1.3	10	36	0.1	43	AS7-5599a
M-07-45	G35586	60	62	0.07	0.11	52	1.1	10	18	0.1	42	AS7-5599a
M-07-45	G35587	62	64	0.05	0.07	20	0.8	10	12	0.1	34	AS7-5599a
M-07-45	G35588	64	66	0.08	0.12	26	1.2	15	20	0.1	45	AS7-5599a
M-07-45	G35589	66	68	0.09	0.12	64	1.1	25	18	5	43	AS7-5599a
M-07-45	G35590	68	70	0.06	0.07	47	0.6	10	18	0.1	17	AS7-5599a
M-07-45	G35591	70	72	0.04	0.02	47	0.5	10	16	0.1	11	AS7-5599a
M-07-45	G35592	72	74	0.04	0.04	37	0.5	25	28	5	11	AS7-5599a
M-07-45	G35593	74	76	0.05	0.02	105	0.5	25	44	5	21	AS7-5603a
M-07-45	G35594	76	78	0.13	0.07	29	0.5	15	18	0.1	246	AS7-5603a
M-07-45	G35595	78	80	0.10	0.10	61	1.2	10	32	0.1	380	AS7-5603a
M-07-45	G35596	80	82	0.10	0.12	32	1.6	15	48	0.1	853	AS7-5603a
M-07-45	G35597	82	84	0.07	0.05	39	0.7	15	76	0.1	518	AS7-5603a
M-07-45	G35598	84	86	0.21	0.10	33	1.3	15	106	0.1	337	AS7-5603a
M-07-45	G35599	86	88	0.16	0.07	65	1	15	182	0.1	216	AS7-5603a
M-07-45	G35600	88	90	0.16	0.08	34	1.2	15	120	0.1	207	AS7-5603a
M-07-45	G35601	90	92	0.20	0.10	51	1.4	15	116	0.1	195	AS7-5603a
M-07-45	G35602	92	94	0.18	0.07	36	1.2	15	68	0.1	305	AS7-5603a
M-07-45	G35604	94	96	0.23	0.09	45	1	15	66	0.1	238	AS7-5603a
M-07-45	G35605	96	98	0.14	0.09	37	1.2	15	122	0.1	267	AS7-5603a
M-07-45	G35606	98	100	0.21	0.12	40	1.4	15	112	0.1	199	AS7-5603a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-45	G35607	100	102	0.78	0.09	84	1	20	38	0.1	148	AS7-5603a
M-07-45	G35608	102	104	0.20	0.09	83	1.2	15	36	0.1	115	AS7-5603a
M-07-45	G35609	104	106	0.20	0.09	35	0.9	20	26	0.1	94	AS7-5603a
M-07-45	G35611	106	108	0.27	0.08	70	0.9	15	30	0.1	107	AS7-5603a
M-07-45	G35612	108	110	0.21	0.05	44	0.7	15	34	0.1	163	AS7-5603a
M-07-45	G35613	110	112	0.18	0.08	56	1	15	36	0.1	92	AS7-5603a
M-07-45	G35614	112	114	0.16	0.08	39	1.5	15	62	0.1	94	AS7-5603a
M-07-45	G35615	114	116	0.22	0.10	66	1.3	15	32	0.1	60	AS7-5603a
M-07-45	G35616	116	118	0.38	0.12	76	1.7	15	56	0.1	63	AS7-5603a
M-07-45	G35617	118	120	0.40	0.08	260	1.4	20	36	0.1	72	AS7-5603a
M-07-45	G35618	120	122	0.33	0.06	52	1.2	15	20	0.1	55	AS7-5603a
M-07-45	G35619	122	124	0.44	0.06	48	1.3	20	30	0.1	84	AS7-5603a
M-07-45	G35620	124	126	0.18	0.06	43	0.9	15	20	0.1	57	AS7-5603a
M-07-45	G35621	126	128	0.21	0.07	55	1.2	10	18	0.1	31	AS7-5603a
M-07-45	G35622	128	130	0.90	0.21	23	4.9	85	72	40	45	AS7-5603a
M-07-45	G35623	130	132	1.49	0.12	23	2.5	15	44	0.1	50	AS7-5603a
M-07-45	G35624	132	134	0.68	0.17	34	5.1	15	32	0.1	77	AS7-5603a
M-07-45	G35625	134	136	0.55	0.09	42	1.1	20	18	0.1	88	AS7-5603a
M-07-45	G35626	136	138	0.59	0.13	43	1.2	15	20	0.1	85	AS7-5603a
M-07-45	G35628	138	140	0.50	0.15	52	1.1	0.1	26	5	86	AS7-5605a
M-07-45	G35629	140	142	0.49	0.08	60	0.9	0.1	18	5	67	AS7-5605a
M-07-45	G35630	142	144	0.81	0.16	53	1.7	0.1	24	10	79	AS7-5605a
M-07-45	G35631	144	146	0.55	0.09	51	1.1	0.1	20	10	100	AS7-5605a
M-07-45	G35632	146	148	0.66	0.14	80	1.7	0.1	24	0.1	79	AS7-5605a
M-07-45	G35633	148	150	1.08	0.13	62	2.6	0.1	56	0.1	67	AS7-5605a
M-07-45	G35634	150	152	0.55	0.08	85	0.9	0.1	24	5	88	AS7-5605a
M-07-45	G35635	152	154	0.81	0.14	52	3.9	0.1	66	0.1	59	AS7-5605a
M-07-45	G35636	154	156	0.96	0.14	76	1.5	0.1	32	5	72	AS7-5605a
M-07-45	G35637	156	157.9	0.76	0.11	47	1.4	0.1	24	5	101	AS7-5605a
M-07-45	G35638	157.9	159.3	0.60	0.10	100	1.2	0.1	34	15	86	AS7-5605a
M-07-45	G35639	159.3	160.7	0.65	0.11	54	1.2	0.1	22	0.1	57	AS7-5605a
M-07-45	G35640	160.7	162	0.67	0.11	53	1.3	0.1	26	0.1	69	AS7-5605a
M-07-45	G35641	162	164	0.53	0.10	257	1.2	0.1	24	10	85	AS7-5605a
M-07-45	G35642	164	166	0.45	0.09	46	1.1	0.1	26	10	83	AS7-5605a
M-07-45	G35643	166	168	0.44	0.08	90	2.6	0.1	30	0.1	74	AS7-5605a
M-07-45	G35644	168	170	0.61	0.11	88	1.1	0.1	26	5	84	AS7-5605a
M-07-45	G35645	170	172	0.80	0.14	55	1.5	0.1	26	10	71	AS7-5605a
M-07-45	G35646	172	174	0.75	0.11	71	1.3	0.1	24	10	70	AS7-5605a
M-07-45	G35647	174	176	1.51	0.14	62	1.5	0.1	38	0.1	56	AS7-5605a
M-07-45	G35648	176	178	0.95	0.15	76	2.2	0.1	52	0.1	52	AS7-5605a
M-07-45	G35649	178	180	1.02	0.15	86	1.6	0.1	30	10	76	AS7-5605a
M-07-45	G35650	180	181.5	0.83	0.12	64	1.5	0.1	20	0.1	68	AS7-5605a
M-07-45	G35651	181.5	183.1	1.25	0.38	62	10.7	95	126	30	115	AS7-5605a
M-07-45	G35652	183.1	185	0.81	0.17	51	2.7	0.1	20	5	75	AS7-5605a
M-07-45	G35653	185	187	0.61	0.11	44	1.5	0.1	26	5	99	AS7-5605a
M-07-45	G35654	187	189	0.64	0.09	38	1.3	0.1	30	0.1	102	AS7-5605a
M-07-45	G35655	189	191	1.24	0.27	39	3.1	0.1	42	0.1	148	AS7-5605a
M-07-45	G35656	191	193	0.76	0.10	29	1.2	0.1	16	0.1	104	AS7-5605a
M-07-45	G35657	193	195	0.66	0.12	29	1.3	0.1	26	0.1	100	AS7-5605a
M-07-45	G35658	195	197	0.93	0.15	45	1.6	0.1	42	5	97	AS7-5605a
M-07-45	G35659	197	199	0.67	0.12	31	1.4	0.1	46	0.1	66	AS7-5605a
M-07-45	G35660	199	201	0.98	0.12	33	1.4	0.1	22	15	87	AS7-5605a
M-07-45	G35663	201	203	0.63	0.12	34	1.5	0.1	24	5	70	AS7-5607a
M-07-45	G35664	203	205	0.69	0.13	48	1.3	0.1	34	15	75	AS7-5607a
M-07-45	G35665	205	207	1.63	0.22	31	2	0.1	26	0.1	62	AS7-5607a
M-07-45	G35666	207	209	0.94	0.15	36	1.9	0.1	28	0.1	52	AS7-5607a
M-07-45	G35667	209	211	0.96	0.24	29	2.3	0.1	28	15	44	AS7-5607a
M-07-45	G35668	211	213	0.71	0.15	19	1.4	5	16	0.1	51	AS7-5607a
M-07-45	G35669	213	215	0.91	0.61	14	6	30	68	15	428	AS7-5607a
M-07-45	G35670	215	217	1.15	0.24	22	2.2	0.1	30	0.1	51	AS7-5607a
M-07-45	G35671	217	219	0.68	0.16	28	1.8	0.1	28	0.1	52	AS7-5607a
M-07-45	G35672	219	221	0.65	0.17	61	1.9	10	38	0.1	60	AS7-5607a
M-07-45	G35674	221	223	0.54	0.12	43	1.5	5	44	0.1	50	AS7-5607a
M-07-45	G35675	223	225	0.53	0.11	33	1.6	5	36	10	63	AS7-5607a
M-07-45	G35676	225	227	0.34	0.10	27	1.3	0.1	46	0.1	36	AS7-5607a
M-07-45	G35677	227	229	0.54	0.12	24	1.5	0.1	32	0.1	44	AS7-5607a
M-07-45	G35678	229	231	0.54	0.14	24	1.2	10	32	0.1	76	AS7-5607a
M-07-45	G35679	231	233	0.70	0.19	26	2.5	10	90	0.1	278	AS7-5607a
M-07-45	G35681	233	235	0.62	0.19	20	2.3	0.1	94	0.1	109	AS7-5607a
M-07-45	G35682	235	237	0.61	0.16	18	1.9	5	40	0.1	101	AS7-5607a
M-07-45	G35683	237	239	0.53	0.12	22	1.8	15	38	0.1	79	AS7-5607a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-45	G35684	239	241	0.47	0.12	29	1.4	15	28	20	81	AS7-5607a
M-07-45	G35685	241	243	0.57	0.12	28	1.8	5	34	0.1	57	AS7-5607a
M-07-45	G35686	243	245	0.67	0.13	26	1.8	15	30	0.1	71	AS7-5607a
M-07-45	G35687	245	247	0.69	0.15	28	3	0.1	58	5	172	AS7-5607a
M-07-45	G35688	247	249	0.53	0.11	31	1.8	5	34	5	94	AS7-5607a
M-07-45	G35689	249	251	0.92	0.17	26	2.1	5	38	20	82	AS7-5607a
M-07-45	G35691	251	253	0.62	0.12	33	1.3	10	34	10	85	AS7-5607a
M-07-45	G35692	253	255	0.87	0.17	28	2.2	15	42	10	124	AS7-5607a
M-07-45	G35693	255	257	0.67	0.13	40	3.1	20	36	10	205	AS7-5607a
M-07-45	G35694	257	259	0.53	0.11	20	3.7	30	64	0.1	80	AS7-5607a
M-07-45	G35695	259	261	0.57	0.11	37	1.9	15	54	15	265	AS7-5607a
M-07-45	G35696	261	263	0.54	0.12	23	1.8	30	38	0.1	125	AS7-5607a
M-07-45	G35697	263	265	0.96	0.30	30	3.3	15	82	0.1	121	AS7-5607a
M-07-45	G35698	265	267	0.81	0.22	36	1.8	10	26	0.1	84	AS7-5610a
M-07-45	G35699	267	269	1.45	0.36	20	5.8	10	30	0.1	93	AS7-5610a
M-07-45	G35700	269	271	0.64	0.14	24	1.8	0.1	32	5	87	AS7-5610a
M-07-45	G35701	271	273	0.72	0.16	22	1.8	0.1	38	10	92	AS7-5610a
M-07-45	G35702	273	275	1.22	0.33	14	3.1	10	72	0.1	72	AS7-5610a
M-07-45	G35703	275	277	0.87	0.20	24	2.5	10	56	10	76	AS7-5610a
M-07-45	G35704	277	279	0.74	0.19	15	2.2	0.1	60	10	79	AS7-5610a
M-07-45	G35705	279	281	1.46	0.18	20	2.5	20	54	20	75	AS7-5610a
M-07-45	G35706	281	283	1.27	0.20	21	96.5	165	106	185	135	AS7-5610a
M-07-45	G35707	283	285	1.11	0.20	16	4.1	50	44	10	41	AS7-5610a
M-07-45	G35708	285	287	0.66	0.15	25	1.9	0.1	36	0.1	69	AS7-5610a
M-07-45	G35709	287	289	0.79	0.20	17	3	15	30	10	60	AS7-5610a
M-07-45	G35710	289	291	1.03	0.21	21	2.6	10	16	0.1	35	AS7-5610a
M-07-45	G35711	291	293	0.84	0.24	22	2.5	0.1	16	0.1	49	AS7-5610a
M-07-45	G35712	293	295	0.83	0.22	23	3.2	0.1	36	0.1	43	AS7-5610a
M-07-45	G35713	295	297	0.92	0.25	23	2.7	0.1	12	0.1	61	AS7-5610a
M-07-45	G35714	297	299	0.68	0.20	17	2.6	0.1	10	0.1	56	AS7-5610a
M-07-45	G35715	299	300	0.59	0.18	25	1.8	0.1	8	5	103	AS7-5610a
M-07-45	G35716	300	300.9	0.05	0.02	1	0.2	0.1	0.1	0.1	3	AS7-5610a
M-07-45	G35717	300.9	303	1.22	0.22	32	2.3	0.1	8	5	67	AS7-5610a
M-07-45	G35718	303	305	0.66	0.19	24	2	0.1	10	0.1	46	AS7-5610a
M-07-45	G35719	305	307	0.57	0.13	24	1.4	0.1	14	10	52	AS7-5610a
M-07-45	G35721	307	309	0.86	0.23	25	2.5	0.1	18	0.1	49	AS7-5610a
M-07-45	G35722	309	311	0.69	0.22	21	2	0.1	12	0.1	42	AS7-5610a
M-07-45	G35723	311	313	0.92	0.23	44	2.2	0.1	14	5	54	AS7-5610a
M-07-45	G35724	313	315	0.97	0.19	40	1.8	0.1	16	30	48	AS7-5610a
M-07-45	G35725	315	317	0.81	0.23	21	2.4	0.1	42	0.1	98	AS7-5610a
M-07-45	G35726	317	319	0.99	0.28	23	2.3	0.1	20	10	151	AS7-5610a
M-07-45	G35727	319	321	1.41	0.26	11	2.1	0.1	30	0.1	103	AS7-5610a
M-07-45	G35728	321	323	1.05	0.28	19	3	0.1	24	15	108	AS7-5610a
M-07-45	G35729	323	325	0.87	0.36	10	6.6	0.1	20	0.1	38	AS7-5610a
M-07-45	G35730	325	327	0.79	0.27	13	3.1	0.1	28	0.1	64	AS7-5610a
M-07-45	G35731	327	329	1.07	0.23	22	2.6	0.1	26	0.1	70	AS7-5610a
M-07-45	G35733	329	331	1.05	0.31	26	2.6	0.1	34	10	74	AS7-5611a
M-07-45	G35734	331	333	0.74	0.17	37	1.7	0.1	30	0.1	52	AS7-5611a
M-07-45	G35735	333	335	1.22	0.27	18	2.3	0.1	30	10	62	AS7-5611a
M-07-45	G35736	335	337	1.16	0.26	12	2.4	5	46	10	42	AS7-5611a
M-07-45	G35737	337	339	0.86	0.25	15	3.6	115	32	15	41	AS7-5611a
M-07-45	G35738	339	341	0.57	0.15	26	1.2	0.1	24	0.1	53	AS7-5611a
M-07-45	G35739	341	343	0.73	0.19	42	1.5	0.1	26	0.1	56	AS7-5611a
M-07-45	G35740	343	345	1.19	0.28	34	2.5	0.1	28	0.1	75	AS7-5611a
M-07-45	G35741	345	347	0.78	0.16	41	1.6	0.1	24	10	82	AS7-5611a
M-07-45	G35742	347	349	1.15	0.24	23	1.9	0.1	30	0.1	38	AS7-5611a
M-07-45	G35743	349	351	0.93	0.27	27	1.7	0.1	24	0.1	26	AS7-5611a
M-07-45	G35744	351	351	0.65	0.17	37	1.3	0.1	20	0.1	46	AS7-5611a
M-07-45	G35746	353	355	0.60	0.18	46	1.6	0.1	26	0.1	48	AS7-5611a
M-07-45	G35747	355	357	0.93	0.23	40	1.5	0.1	26	0.1	42	AS7-5611a
M-07-45	G35748	357	359	0.81	0.22	34	2.5	5	28	0.1	38	AS7-5611a
M-07-45	G35749	359	361	1.02	0.29	28	3.4	0.1	28	0.1	51	AS7-5611a
M-07-45	G35750	361	363	1.00	0.27	38	3.4	0.1	28	15	67	AS7-5611a
M-07-45	G35751	363	365	0.67	0.16	35	3.4	15	42	10	90	AS7-5611a
M-07-45	G35752	365	367	0.84	0.15	26	3.4	30	42	15	36	AS7-5611a
M-07-45	G35753	367	369	0.67	0.23	42	2.3	0.1	20	5	42	AS7-5611a
M-07-45	G35754	369	371	0.84	0.24	31	2.3	0.1	22	10	58	AS7-5611a
M-07-45	G35755	371	373	0.84	0.24	33	2	0.1	24	10	57	AS7-5611a
M-07-45	G35756	373	375	0.82	0.19	58	1.7	0.1	26	10	60	AS7-5611a
M-07-45	G35757	375	377	0.60	0.21	48	1.9	0.1	38	0.1	58	AS7-5611a
M-07-45	G35758	377	379	0.95	0.21	37	2.3	0.1	30	10	72	AS7-5611a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-45	G35759	379	381	1.16	0.26	25	2.2	0.1	40	0.1	39	AS7-5611a
M-07-45	G35760	381	383	1.00	0.21	18	2.1	0.1	36	0.1	58	AS7-5611a
M-07-45	G35761	383	385	0.83	0.23	41	2.1	0.1	20	0.1	87	AS7-5611a
M-07-45	G35762	385	387	0.72	0.24	19	2.3	0.1	42	5	75	AS7-5611a
M-07-45	G35763	387	389	1.01	0.27	19	2.2	0.1	28	5	61	AS7-5611a
M-07-45	G35764	389	391	0.66	0.21	38	1.6	0.1	22	0.1	56	AS7-5611a
M-07-45	G35765	391	393	1.23	0.30	27	2.8	0.1	34	20	67	AS7-5611a
M-07-45	G35768	393	395	0.89	0.21	24	1.8	0.1	24	10	53	AS7-5613a
M-07-45	G35769	395	397	1.10	0.24	24	2.1	0.1	20	20	70	AS7-5613a
M-07-45	G35770	397	399	1.62	0.39	16	2.7	0.1	20	0.1	36	AS7-5613a
M-07-45	G35771	399	401	1.06	0.21	41	1.8	15	22	10	57	AS7-5613a
M-07-45	G35773	401	403	1.08	0.26	34	2	0.1	20	0.1	56	AS7-5613a
M-07-45	G35774	403	405	1.33	0.27	17	2.4	0.1	36	0.1	69	AS7-5613a
M-07-45	G35775	405	407	1.40	0.25	21	2.2	0.1	36	0.1	60	AS7-5613a
M-07-45	G35776	407	409	1.08	0.26	22	2.4	15	38	10	117	AS7-5613a
M-07-45	G35777	409	411	1.05	0.23	21	1.8	10	28	10	49	AS7-5613a
M-07-45	G35778	411	413	1.09	0.20	30	1.7	15	20	10	32	AS7-5613a
M-07-45	G35779	413	415	1.01	0.22	29	2	0.1	14	10	46	AS7-5613a
M-07-45	G35780	415	417	0.74	0.23	32	2.2	15	22	0.1	11	AS7-5613a
M-07-45	G35781	417	419	1.42	0.24	37	2.8	0.1	20	10	61	AS7-5613a
M-07-45	G35782	419	421	1.67	0.23	37	2.1	0.1	36	10	52	AS7-5613a
M-07-45	G35784	421	423	2.12	0.29	41	3.6	0.1	18	10	48	AS7-5613a
M-07-45	G35785	423	425	1.13	0.23	36	1.9	0.1	18	10	42	AS7-5613a
M-07-45	G35786	425	427	1.89	0.30	43	2.2	0.1	54	10	51	AS7-5613a
M-07-45	G35787	427	429	1.22	0.22	43	1.7	0.1	20	0.1	60	AS7-5613a
M-07-45	G35788	429	431	1.24	0.20	37	1.2	0.1	18	0.1	63	AS7-5613a
M-07-45	G35789	431	433	1.61	0.28	72	1.8	0.1	20	15	48	AS7-5613a
M-07-45	G35790	433	435	1.27	0.33	99	2.3	0.1	18	0.1	26	AS7-5613a
M-07-45	G35791	435	437	0.76	0.24	50	1.5	0.1	20	10	35	AS7-5613a
M-07-45	G35792	437	439	1.28	0.24	48	1.4	15	14	5	23	AS7-5613a
M-07-45	G35793	439	441	1.29	0.27	51	1.9	0.1	14	10	27	AS7-5613a
M-07-45	G35794	441	443	1.31	0.25	42	1.7	0.1	14	0.1	29	AS7-5613a
M-07-45	G35795	443	445	0.80	0.19	38	1.3	0.1	16	10	42	AS7-5613a
M-07-45	G35796	445	447	1.45	0.31	40	2.3	0.1	18	0.1	31	AS7-5613a
M-07-45	G35797	447	449	1.29	0.26	40	1.6	0.1	20	5	39	AS7-5613a
M-07-45	G35798	449	451	0.80	0.17	30	1.4	0.1	22	10	53	AS7-5613a
M-07-45	G35799	451	453	1.08	0.19	40	1.6	30	16	5	23	AS7-5613a
M-07-45	G35800	453	455	1.04	0.18	44	1.7	15	18	15	27	AS7-5613a
M-07-45	G35801	455	457	1.24	0.23	40	1.7	0.1	16	0.1	33	AS7-5613a
M-07-45	G35802	457	459	2.09	0.20	45	2.2	20	14	10	37	AS7-5613a
M-07-45	G35803	459	461	1.98	0.22	43	4.5	60	18	20	23	AS7-5612a
M-07-45	G35804	461	463	4.10	0.21	37	75	100	652	110	282	AS7-5612a
M-07-45	G35805	463	465	2.85	0.31	54	242	230	302	375	565	AS7-5612a
M-07-45	G35806	465	467	1.21	0.26	75	3.6	0.1	28	15	49	AS7-5612a
M-07-45	G35807	467	469	0.94	0.21	68	2.5	0.1	22	10	59	AS7-5612a
M-07-45	G35808	469	471	1.12	0.23	72	2.4	0.1	22	10	53	AS7-5612a
M-07-45	G35809	471	473	0.92	0.20	60	2.2	0.1	20	10	46	AS7-5612a
M-07-45	G35811	473	475	0.99	0.19	74	2.4	0.1	20	10	48	AS7-5612a
M-07-45	G35812	475	477	1.02	0.22	65	2.7	0.1	24	5	38	AS7-5612a
M-07-45	G35813	477	479	1.25	0.24	87	2.9	0.1	22	0.1	39	AS7-5612a
M-07-45	G35814	479	481	1.07	0.23	78	2	0.1	24	10	48	AS7-5612a
M-07-45	G35815	481	483	1.39	0.29	107	2.5	0.1	26	5	31	AS7-5612a
M-07-45	G35816	483	485	1.11	0.22	71	4.1	0.1	24	5	50	AS7-5612a
M-07-45	G35817	485	487	1.40	0.27	73	4.1	0.1	20	10	64	AS7-5612a
M-07-45	G35818	487	489	0.76	0.20	37	2.7	0.1	42	5	77	AS7-5612a
M-07-45	G35819	489	491	0.73	0.19	47	2.9	0.1	26	5	43	AS7-5612a
M-07-45	G35821	491	493	0.68	0.18	69	3.3	0.1	30	5	73	AS7-5612a
M-07-45	G35823	493	495	0.66	0.20	54	3.1	0.1	22	5	45	AS7-5612a
M-07-45	G35824	495	497	0.59	0.19	64	3.8	0.1	34	5	68	AS7-5612a
M-07-45	G35825	497	499	0.46	0.19	50	3.7	0.1	40	10	45	AS7-5612a
M-07-45	G35826	499	501	0.84	0.21	89	7.2	15	20	10	31	AS7-5612a
M-07-45	G35827	501	503	0.68	0.31	53	74.5	105	18	220	52	AS7-5612a
M-07-45	G35828	503	505	0.87	0.19	84	25	60	30	115	59	AS7-5612a
M-07-45	G35829	505	507	1.04	0.23	109	3.2	0.1	22	10	35	AS7-5612a
M-07-45	G35830	507	509	0.75	0.17	60	2.5	5	24	5	43	AS7-5612a
M-07-45	G35831	509	511	0.52	0.17	88	6.1	20	22	20	50	AS7-5612a
M-07-45	G35832	511	513	0.97	0.18	83	13.8	50	30	30	69	AS7-5612a
M-07-45	G35833	513	515	0.97	0.28	91	7.9	20	20	10	32	AS7-5612a
M-07-45	G35834	515	517	0.70	0.19	71	5	0.1	26	10	35	AS7-5612a
M-07-45	G35835	517	519	0.90	0.20	191	7	35	28	20	45	AS7-5612a
M-07-45	G35836	519	521	1.62	0.24	90	5	15	26	10	30	AS7-5612a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-45	G35837	521	523	5.40	0.21	106	4.7	75	34	15	42	AS7-5612a
M-07-45	G35838	523	525	14.40	0.18	45	76.9	245	76	230	79	AS7-5621a
M-07-45	G35839	525	527	1.31	0.32	51	18	10	32	10	36	AS7-5621a
M-07-45	G35840	527	529	1.02	0.26	111	5.7	0.1	18	5	31	AS7-5621a
M-07-45	G35841	529	531	1.06	0.24	58	5.3	25	24	25	36	AS7-5621a
M-07-45	G35842	531	533	0.64	0.18	82	3.3	20	20	10	39	AS7-5621a
M-07-45	G35843	533	535	0.85	0.26	62	4.2	10	22	5	30	AS7-5621a
M-07-45	G35844	535	537	1.07	0.14	64	2.1	30	18	5	29	AS7-5621a
M-07-45	G35845	537	539	0.73	0.17	62	2.3	5	18	0.1	22	AS7-5621a
M-07-45	G35846	539	541	0.76	0.22	54	4.9	0.1	32	5	30	AS7-5621a
M-07-45	G35847	541	543	0.60	0.21	73	7.9	15	28	0.1	34	AS7-5621a
M-07-45	G35848	543	545	0.92	0.25	72	13.4	0.1	782	5	58	AS7-5621a
M-07-45	G35849	545	547	0.68	0.16	52	4.1	10	24	0.1	34	AS7-5621a
M-07-45	G35850	547	549	0.63	0.13	103	1.5	0.1	24	10	30	AS7-5621a
M-07-45	G35851	549	551	0.87	0.20	96	2.5	0.1	22	5	29	AS7-5621a
M-07-45	G35852	551	553	1.07	0.25	100	3.3	0.1	20	10	28	AS7-5621a
M-07-45	G35853	553	555	1.16	0.21	72	2.7	0.1	20	0.1	24	AS7-5621a
M-07-45	G35854	555	557	0.82	0.20	80	2	0.1	22	0.1	32	AS7-5621a
M-07-45	G35855	557	559	0.67	0.18	57	2.1	0.1	26	0.1	34	AS7-5621a
M-07-45	G35856	559	561	0.62	0.17	102	4.1	0.1	52	0.1	59	AS7-5621a
M-07-45	G35857	561	563	0.63	0.18	69	2.7	1650	0.1	0.1	26	AS7-5621a
M-07-45	G35858	563	565	0.81	0.15	93	2.8	10	30	0.1	43	AS7-5621a
M-07-45	G35860	565	567	0.63	0.21	95	5.1	550	92	85	66	AS7-5621a
M-07-45	G35861	567	569	0.52	0.09	62	3.9	5	34	10	58	AS7-5621a
M-07-45	G35862	569	571	0.76	0.26	104	5.5	10	44	10	34	AS7-5621a
M-07-45	G35863	571	573	0.81	0.17	91	2	10	30	20	30	AS7-5621a
M-07-45	G35864	573	575	0.61	0.15	84	1.9	0.1	26	0.1	31	AS7-5621a
M-07-45	G35865	575	577	0.58	0.11	65	1.3	20	28	0.1	32	AS7-5621a
M-07-45	G35866	577	579	0.60	0.16	100	2.1	0.1	28	5	31	AS7-5621a
M-07-45	G35867	579	581	0.66	0.17	71	2.9	15	36	10	99	AS7-5621a
M-07-45	G35868	581	583	0.81	0.19	73	2.5	15	30	0.1	45	AS7-5621a
M-07-45	G35869	583	585	0.58	0.14	83	1.8	25	26	5	36	AS7-5621a
M-07-45	G35870	585	587	0.60	0.11	77	1.7	10	30	0.1	49	AS7-5621a
M-07-45	G35873	587	589	0.56	0.15	58	2	0.1	22	10	48	AS7-5622a
M-07-45	G35874	589	591	0.60	0.17	133	2	0.1	22	5	28	AS7-5622a
M-07-45	G35875	591	593	0.61	0.15	78	2	0.1	24	5	33	AS7-5622a
M-07-45	G35876	593	595	0.60	0.19	162	3.1	10	24	10	35	AS7-5622a
M-07-45	G35877	595	597	0.47	0.14	132	2.7	10	26	5	37	AS7-5622a
M-07-45	G35878	597	599	0.60	0.20	130	3.2	0.1	24	0.1	32	AS7-5622a
M-07-45	G35879	599	601	0.53	0.14	102	3.5	15	26	10	36	AS7-5622a
M-07-45	G35880	601	603	0.60	0.12	137	8.7	45	28	10	30	AS7-5622a
M-07-45	G35881	603	605	0.87	0.16	106	43.9	150	682	80	110	AS7-5622a
M-07-45	G35882	605	607	0.59	0.10	80	3.2	25	20	0.1	24	AS7-5622a
M-07-45	G35883	607	609.2	0.52	0.11	56	4	0.1	24	15	51	AS7-5622a
M-07-45	G35884	609.2	611	0.69	0.18	154	3.4	0.1	22	5	31	AS7-5622a
M-07-45	G35885	611	613	0.50	0.19	173	2.8	15	30	0.1	25	AS7-5622a
M-07-45	G35887	613	615	0.45	0.16	78	2.1	0.1	20	0.1	38	AS7-5622a
M-07-45	G35888	615	617	0.45	0.14	205	1.6	0.1	22	0.1	21	AS7-5622a
M-07-45	G35889	617	619	0.33	0.10	65	2.7	0.1	22	0.1	19	AS7-5622a
M-07-45	G35890	619	621	0.37	0.14	123	5.7	0.1	22	0.1	16	AS7-5622a
M-07-45	G35891	621	623	0.29	0.10	54	4.6	0.1	24	5	25	AS7-5622a
M-07-45	G35892	623	624.65	0.36	0.07	45	5.6	10	28	5	23	AS7-5622a
M-07-45	G35893	624.65	626	0.40	0.12	123	5.6	0.1	24	0.1	26	AS7-5622a
M-07-45	G35894	626	628	0.30	0.11	178	3	0.1	26	10	33	AS7-5622a
M-07-45	G35895	628	630	0.52	0.14	80	3.5	15	22	0.1	34	AS7-5622a
M-07-45	G35897	630	632	0.30	0.08	139	2.3	0.1	32	0.1	39	AS7-5622a
M-07-45	G35898	632	634	0.28	0.15	242	10.9	10	70	15	78	AS7-5622a
M-07-45	G35899	634	636	0.41	0.13	84	3.8	0.1	22	10	28	AS7-5622a
M-07-45	G35900	636	638	0.33	0.10	132	2	5	24	5	27	AS7-5622a
M-07-45	G35901	638	640	0.42	0.12	225	2.6	10	22	0.1	27	AS7-5622a
M-07-45	G35902	640	642	0.33	0.10	155	2.5	0.1	32	10	37	AS7-5622a
M-07-45	G35903	642	644.15	0.28	0.10	109	5.5	20	42	10	50	AS7-5622a
M-07-45	G35904	644.15	646.25	0.28	0.21	230	90.3	165	594	225	266	AS7-5622a
M-07-45	G35905	646.25	648.25	0.55	0.08	133	10.5	5	90	15	33	AS7-5622a
M-07-45	G35906	648.25	649.5	0.25	0.10	81	4.5	0.1	26	0.1	42	AS7-5622a
M-07-45	G35907	649.5	650.72	0.34	0.11	115	4.2	0.1	34	5	46	AS7-5622a
M-07-46	X09172	2.25	4	0.52	0.12	40	1.9	0.1	34	5	60	AS7-5606a
M-07-46	X09173	4	6	0.45	0.14	47	1.7	0.1	26	0.1	57	AS7-5606a
M-07-46	X09174	6	8	0.44	0.14	54	1.8	0.1	22	0.1	56	AS7-5606a
M-07-46	X09175	8	10	0.53	0.15	29	1.7	0.1	22	0.1	54	AS7-5606a
M-07-46	X09176	10	11	0.61	0.17	39	2.2	0.1	18	0.1	60	AS7-5606a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-46	X09177	11.9	14	0.31	0.10	25	1.2	0.1	14	0.1	56	AS7-5606a
M-07-46	X09178	14	16	0.59	0.16	47	1.8	0.1	18	0.1	52	AS7-5606a
M-07-46	X09179	16	18	0.35	0.09	30	1.1	0.1	14	10	40	AS7-5606a
M-07-46	X09180	18	20	0.46	0.12	30	1.6	0.1	16	0.1	43	AS7-5606a
M-07-46	X09182	20	22	0.46	0.12	46	1.4	0.1	18	10	44	AS7-5606a
M-07-46	X09183	22	23.85	0.47	0.12	47	1.5	0.1	16	5	45	AS7-5606a
M-07-46	X09184	24.45	26	0.58	0.14	37	1.7	0.1	20	10	52	AS7-5606a
M-07-46	X09185	26	28	0.77	0.19	62	2	0.1	18	10	55	AS7-5606a
M-07-46	X09186	28	30	0.64	0.17	40	1.9	0.1	16	5	46	AS7-5606a
M-07-46	X09187	30	32	0.47	0.17	34	1.7	0.1	16	0.1	44	AS7-5606a
M-07-46	X09188	32	34	0.55	0.13	34	1.8	0.1	18	5	47	AS7-5606a
M-07-46	X09189	34	36	0.72	0.21	56	2.1	0.1	20	0.1	45	AS7-5606a
M-07-46	X09190	36	38	0.75	0.17	28	1.6	0.1	18	5	54	AS7-5606a
M-07-46	X09192	38	40	0.69	0.18	64	2.1	0.1	24	10	51	AS7-5606a
M-07-46	X09193	40	42	0.42	0.13	55	1.7	0.1	20	10	51	AS7-5606a
M-07-46	X09194	42	44	0.26	0.09	31	2	0.1	18	10	52	AS7-5606a
M-07-46	X09195	44	46	0.42	0.15	33	74	35	136	10	54	AS7-5606a
M-07-46	X09196	46	48	0.45	0.12	40	2.8	40	20	10	41	AS7-5606a
M-07-46	X09197	48	49.6	0.51	0.16	43	14.7	185	38	10	64	AS7-5606a
M-07-46	X09198	49.6	51	0.00	0.00	9	0.8	15	30	20	83	AS7-5606a
M-07-46	X09199	51	52.55	0.00	0.00	6	0.2	30	32	15	76	AS7-5606a
M-07-46	X09201	58.7	60	0.51	0.09	32	4.5	95	30	10	63	AS7-5606a
M-07-46	X09202	60	62	0.38	0.10	22	2.8	40	48	10	80	AS7-5606a
M-07-46	X09204	62	64	0.23	0.08	23	1.2	15	24	10	81	AS7-5606a
M-07-46	X09205	64	66	0.24	0.08	37	0.9	0.1	20	0.1	59	AS7-5606a
M-07-46	X09206	66	68	0.37	0.15	33	1.5	5	20	5	53	AS7-5606a
M-07-46	X09207	68	70	0.45	0.18	95	2.1	30	48	20	64	AS7-5608a
M-07-46	X09208	70	72	0.79	0.28	31	3.4	15	32	0.1	47	AS7-5608a
M-07-46	X09209	72	74	0.62	0.18	30	2.7	20	32	5	62	AS7-5608a
M-07-46	X09210	74	76	0.33	0.14	28	2.3	10	30	5	66	AS7-5608a
M-07-46	X09211	76	78	0.56	0.14	26	1.9	15	32	0.1	59	AS7-5608a
M-07-46	X09212	78	80	0.56	0.19	26	2.2	10	30	0.1	62	AS7-5608a
M-07-46	X09213	80	82	0.38	0.10	19	1.2	10	28	0.1	64	AS7-5608a
M-07-46	X09214	82	84	0.47	0.15	30	1.8	0.1	24	25	69	AS7-5608a
M-07-46	X09216	84	86	0.41	0.11	32	1.4	0.1	34	0.1	93	AS7-5608a
M-07-46	X09217	86	88	0.33	0.11	22	1.2	0.1	32	0.1	78	AS7-5608a
M-07-46	X09218	88	90	0.49	0.12	30	1.4	15	40	5	87	AS7-5608a
M-07-46	X09219	90	92	0.40	0.12	38	1.6	15	40	15	80	AS7-5608a
M-07-46	X09220	92	94	0.56	0.15	39	1.9	10	32	0.1	74	AS7-5608a
M-07-46	X09221	94	96	0.37	0.13	29	1.4	5	44	5	67	AS7-5608a
M-07-46	X09222	96	98	0.43	0.12	26	2	10	30	0.1	63	AS7-5608a
M-07-46	X09223	98	100	0.79	0.24	24	3.1	0.1	38	0.1	71	AS7-5608a
M-07-46	X09224	100	102	0.43	0.14	36	1.9	0.1	30	0.1	71	AS7-5608a
M-07-46	X09226	102	104	0.53	0.15	36	1.8	5	40	10	80	AS7-5608a
M-07-46	X09227	104	105	0.41	0.15	32	1.5	0.1	30	5	76	AS7-5608a
M-07-46	X09228	105	106.3	0.34	0.12	35	1.4	10	38	20	89	AS7-5608a
M-07-46	X09229	106.3	108	0.56	0.19	34	2.8	20	58	10	53	AS7-5608a
M-07-46	X09230	108	110	0.44	0.14	24	2.5	20	42	0.1	65	AS7-5608a
M-07-46	X09231	110	112	0.50	0.18	51	2.1	5	44	10	81	AS7-5608a
M-07-46	X09232	112	114	0.71	0.20	24	3.4	20	52	15	71	AS7-5608a
M-07-46	X09233	114	115.8	0.35	0.10	25	1.5	20	38	15	73	AS7-5608a
M-07-46	X09234	115.8	117.5	0.49	0.10	36	3	30	392	15	466	AS7-5608a
M-07-46	X09235	117.5	119	0.51	0.15	38	2.3	15	72	25	119	AS7-5608a
M-07-46	X09236	119	121	0.37	0.13	38	1.8	0.1	34	5	75	AS7-5608a
M-07-46	X09237	121	123	0.41	0.11	35	1.7	20	38	10	82	AS7-5608a
M-07-46	X09238	123	125	0.22	0.09	34	1.3	20	38	5	92	AS7-5608a
M-07-46	X09239	125	127	0.29	0.15	36	1.5	5	42	10	97	AS7-5608a
M-07-46	X09240	127	129	0.31	0.11	35	1.6	20	32	10	81	AS7-5608a
M-07-46	X09241	129	131.2	0.29	0.11	37	1.4	20	40	0.1	72	AS7-5608a
M-07-46	X09242	131.2	133	0.29	0.12	29	1.6	0.1	28	15	89	AS7-5609a
M-07-46	X09243	133	135	0.31	0.14	27	1.2	0.1	28	5	79	AS7-5609a
M-07-46	X09244	135	137	0.24	0.13	52	1.5	5	28	10	66	AS7-5609a
M-07-46	X09245	137	139	0.27	0.13	48	1.6	5	30	20	68	AS7-5609a
M-07-46	X09247	139	141	0.43	0.16	38	2.7	25	50	15	78	AS7-5609a
M-07-46	X09248	141	143	0.31	0.15	47	2	0.1	38	15	81	AS7-5609a
M-07-46	X09249	143	145	0.27	0.13	47	1.8	0.1	38	10	85	AS7-5609a
M-07-46	X09250	145	147	0.21	0.12	59	1.5	0.1	34	15	81	AS7-5609a
M-07-46	X09251	147	149	0.25	0.12	65	1.5	5	30	0.1	62	AS7-5609a
M-07-46	X09252	149	151	0.25	0.11	46	1.4	0.1	32	25	77	AS7-5609a
M-07-46	X09253	151	153	0.22	0.11	54	1.6	10	50	30	80	AS7-5609a
M-07-46	X09254	153	155	0.19	0.11	86	1.6	10	28	10	70	AS7-5609a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-46	X09255	155	157	0.22	0.10	57	1.5	5	32	15	71	AS7-5609a
M-07-46	X09257	157	159	0.27	0.13	64	1.9	5	28	10	80	AS7-5609a
M-07-46	X09258	159	160.1	0.23	0.12	58	1.6	10	30	20	82	AS7-5609a
M-07-46	X09259	160.1	162	0.22	0.11	41	1.7	10	28	10	55	AS7-5609a
M-07-46	X09260	162	164	0.27	0.12	42	1.9	0.1	28	20	46	AS7-5609a
M-07-46	X09261	164	166	0.24	0.12	38	1.8	10	24	10	70	AS7-5609a
M-07-46	X09262	166	168	0.34	0.17	34	1.8	0.1	24	10	58	AS7-5609a
M-07-46	X09263	168	169.55	0.30	0.12	59	1.6	10	34	15	68	AS7-5609a
M-07-46	X09264	170.1	172	0.30	0.12	62	1.9	10	24	10	59	AS7-5609a
M-07-46	X09265	172	174	0.24	0.10	44	1.5	5	24	10	53	AS7-5609a
M-07-46	X09266	174	176	0.36	0.11	60	3.1	10	68	20	98	AS7-5609a
M-07-46	X09267	176	178	0.30	0.12	46	2.9	0.1	154	15	242	AS7-5609a
M-07-46	X09268	178	180	0.42	0.12	68	2.9	5	34	15	64	AS7-5609a
M-07-46	X09270	180	182	0.19	0.10	69	1.7	0.1	28	10	85	AS7-5609a
M-07-46	X09271	182	184	0.19	0.09	46	2.9	0.1	28	10	80	AS7-5609a
M-07-46	X09272	184	186	0.20	0.10	21	6.8	15	102	10	110	AS7-5609a
M-07-46	X09273	186	188	0.24	0.15	55	2.9	10	34	10	64	AS7-5609a
M-07-46	X09274	188	189.25	0.20	0.12	86	3.8	0.1	36	15	75	AS7-5609a
M-07-46	X09275	189.25	191	0.27	0.10	69	1.6	0.1	26	0.1	76	AS7-5609a
M-07-46	X09276	191	193	0.24	0.13	76	1.3	0.1	28	10	73	AS7-5609a
M-07-46	X09277	193	195	0.19	0.07	71	0.3	0.1	24	10	65	AS7-5614a
M-07-46	X09278	195	197	0.24	0.11	53	0.6	0.1	20	10	86	AS7-5614a
M-07-46	X09279	197	199	0.23	0.12	56	1	0.1	12	10	72	AS7-5614a
M-07-46	X09281	199	201	0.40	0.20	33	1.4	0.1	18	0.1	78	AS7-5614a
M-07-46	X09282	201	203	0.25	0.12	63	1	0.1	22	10	76	AS7-5614a
M-07-46	X09283	203	204.85	0.26	0.16	47	1	0.1	22	10	93	AS7-5614a
M-07-46	X09284	204.85	206	0.28	0.13	53	1.2	0.1	24	15	71	AS7-5614a
M-07-46	X09285	206	208	0.26	0.12	54	1.1	0.1	18	10	79	AS7-5614a
M-07-46	X09286	208	210	0.26	0.13	47	0.8	0.1	16	10	59	AS7-5614a
M-07-46	X09287	210	212	0.29	0.10	30	1.7	10	48	10	76	AS7-5614a
M-07-46	X09288	212	214	0.53	0.29	32	1.9	15	20	15	69	AS7-5614a
M-07-46	X09290	214	216	0.56	0.20	81	2.4	15	52	5	97	AS7-5614a
M-07-46	X09291	216	218	0.39	0.25	97	2.3	0.1	22	10	64	AS7-5614a
M-07-46	X09292	218	220	0.36	0.14	30	1.4	0.1	16	10	59	AS7-5614a
M-07-46	X09293	220	221	0.59	0.17	62	1.9	0.1	358	5	64	AS7-5614a
M-07-46	X09294	221	222.35	0.32	0.15	65	2	5	24	10	79	AS7-5614a
M-07-46	X09295	222.35	224	0.35	0.13	65	1	0.1	16	5	71	AS7-5614a
M-07-46	X09296	224	226	0.47	0.15	36	0.9	0.1	14	10	57	AS7-5614a
M-07-46	X09297	226	228	0.56	0.26	19	1.6	0.1	18	10	52	AS7-5614a
M-07-46	X09298	228	230	0.32	0.17	155	1.1	0.1	18	10	61	AS7-5614a
M-07-46	X09299	230	232	0.34	0.18	47	1	0.1	18	0.1	72	AS7-5614a
M-07-46	X09300	232	234	0.34	0.13	53	0.8	0.1	20	10	80	AS7-5614a
M-07-46	X09301	234	236	0.40	0.16	24	1.1	0.1	18	10	74	AS7-5614a
M-07-46	X09302	236	238	0.39	0.21	48	3.6	0.1	76	15	1623	AS7-5614a
M-07-46	X09304	238	240	0.46	0.12	42	0.8	0.1	16	5	86	AS7-5614a
M-07-46	X09305	240	242	0.39	0.17	28	1.6	0.1	24	20	98	AS7-5614a
M-07-46	X09306	242	244	0.26	0.15	39	1.9	0.1	60	10	86	AS7-5614a
M-07-46	X09307	244	246	0.19	0.12	49	1.7	0.1	22	0.1	72	AS7-5614a
M-07-46	X09308	246	248	0.09	0.13	32	1.4	0.1	18	0.1	91	AS7-5614a
M-07-46	X09309	248	248.65	0.00	0.02	14	0.4	0.1	26	30	169	AS7-5614a
M-07-46	X09310	248.65	249.5	0.21	0.12	23	1.4	0.1	32	0.1	75	AS7-5614a
M-07-46	X09311	249.5	251	0.00	0.01	10	0.01	10	24	35	64	AS7-5614a
M-07-46	X09312	251	253	0.31	0.11	59	1.1	0.1	18	10	81	AS7-5617a
M-07-46	X09313	253	255	0.27	0.09	50	0.8	0.1	20	5	79	AS7-5617a
M-07-46	X09314	255	257	0.40	0.13	128	1.4	0.1	30	0.1	84	AS7-5617a
M-07-46	X09315	257	259	0.27	0.11	109	1.2	0.1	20	10	79	AS7-5617a
M-07-46	X09316	259	261	0.23	0.09	45	1.3	0.1	30	0.1	92	AS7-5617a
M-07-46	X09317	261	263	0.31	0.10	35	1.1	0.1	30	0.1	92	AS7-5617a
M-07-46	X09318	263	265	0.32	0.12	39	1.1	0.1	18	0.1	77	AS7-5617a
M-07-46	X09319	265	267	0.37	0.13	104	1.8	0.1	28	10	92	AS7-5617a
M-07-46	X09320	267	268	0.35	0.13	41	3	5	50	0.1	67	AS7-5617a
M-07-46	X09321	268	269.43	0.36	0.13	59	2	0.1	82	5	82	AS7-5617a
M-07-46	X09322	270.58	272	0.24	0.11	54	1.2	0.1	20	10	64	AS7-5617a
M-07-46	X09323	272	274	0.18	0.08	36	0.9	0.1	18	10	62	AS7-5617a
M-07-46	X09324	274	276	0.26	0.12	30	1.3	0.1	18	0.1	61	AS7-5617a
M-07-46	X09326	276	278	0.22	0.10	23	1.2	0.1	20	5	57	AS7-5617a
M-07-46	X09327	278	280	0.12	0.06	25	0.8	0.1	18	0.1	53	AS7-5617a
M-07-46	X09328	280	282	0.21	0.09	99	1.1	0.1	16	0.1	65	AS7-5617a
M-07-46	X09329	282	284	0.42	0.15	46	2	0.1	16	0.1	60	AS7-5617a
M-07-46	X09330	284	286	0.40	0.15	49	1.8	0.1	42	5	80	AS7-5617a
M-07-46	X09331	286	288	0.19	0.08	45	1	0.1	22	0.1	61	AS7-5617a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-46	X09332	288	290	0.14	0.08	27	1	0.1	32	5	69	AS7-5617a
M-07-46	X09334	290	292	0.16	0.09	48	1.1	0.1	26	5	74	AS7-5617a
M-07-46	X09335	292	294	0.26	0.13	84	1.3	0.1	24	5	68	AS7-5617a
M-07-46	X09336	294	296	0.28	0.11	99	2	0.1	20	5	52	AS7-5617a
M-07-46	X09337	296	298	0.13	0.06	53	0.7	0.1	16	5	76	AS7-5617a
M-07-46	X09338	298	300	0.14	0.12	92	1.3	0.1	16	5	58	AS7-5617a
M-07-46	X09339	300	302	0.20	0.10	110	0.9	0.1	18	5	53	AS7-5617a
M-07-46	X09340	302	304	0.22	0.08	285	1	0.1	18	0.1	69	AS7-5617a
M-07-46	X09342	304	305.8	0.52	0.27	85	3.2	10	156	10	191	AS7-5617a
M-07-46	X09343	305.8	307.35	0.28	0.11	74	1.5	0.1	18	5	53	AS7-5617a
M-07-46	X09344	307.35	309	0.10	0.06	83	0.8	0.1	22	10	59	AS7-5617a
M-07-46	X09345	309	310.4	0.13	0.09	70	1.1	0.1	14	0.1	63	AS7-5617a
M-07-46	X09346	310.4	312.4	0.19	0.11	66	1.2	0.1	34	0.1	126	AS7-5617a
M-07-46	X09347	312.4	314.6	0.14	0.19	326	2.1	0.1	70	0.1	382	AS7-5618a
M-07-46	X09348	314.6	316	0.61	0.26	667	2.6	5	30	10	135	AS7-5618a
M-07-46	X09349	316	318	0.27	0.13	187	2	0.1	72	10	83	AS7-5618a
M-07-46	X09350	318	320	0.19	0.13	85	3	0.1	76	5	75	AS7-5618a
M-07-46	X09351	320	322	0.23	0.11	376	1.8	0.1	50	10	74	AS7-5618a
M-07-46	X09352	322	324	0.34	0.21	179	2.9	0.1	76	10	76	AS7-5618a
M-07-46	X09353	324	326	0.17	0.07	687	0.9	0.1	32	10	59	AS7-5618a
M-07-46	X09354	326	328	0.16	0.06	59	0.9	0.1	18	10	55	AS7-5618a
M-07-46	X09355	328	330	0.28	0.13	198	2.3	0.1	16	10	50	AS7-5618a
M-07-46	X09357	330	331	0.22	0.12	37	2.1	5	50	10	48	AS7-5618a
M-07-46	X09358	331	333	0.13	0.09	160	1.4	0.1	16	5	65	AS7-5618a
M-07-46	X09359	333	335	0.15	0.08	83	1	0.1	22	10	104	AS7-5618a
M-07-46	X09360	335	337	0.16	0.10	89	1.3	0.1	22	0.1	85	AS7-5618a
M-07-46	X09361	337	339	0.22	0.18	384	2	5	28	5	61	AS7-5618a
M-07-46	X09362	339	341	0.38	0.15	444	1.5	0.1	20	10	62	AS7-5618a
M-07-46	X09363	341	343	0.24	0.11	359	1.5	5	16	5	49	AS7-5618a
M-07-46	X09364	343	345	0.15	0.07	70	1	0.1	16	0.1	54	AS7-5618a
M-07-46	X09365	345	347	0.19	0.10	261	1	0.1	22	10	54	AS7-5618a
M-07-46	X09366	347	349	0.21	0.12	327	1.6	10	22	0.1	62	AS7-5618a
M-07-46	X09368	349	351	0.35	0.15	711	1.9	5	20	0.1	38	AS7-5618a
M-07-46	X09369	351	353	0.24	0.13	162	2	10	32	10	48	AS7-5618a
M-07-46	X09370	353	355	0.34	0.14	207	2.5	0.1	260	5	64	AS7-5618a
M-07-46	X09371	355	357	0.29	0.11	208	2.2	0.1	24	5	54	AS7-5618a
M-07-46	X09372	357	359	0.15	0.09	354	1.6	0.1	20	10	51	AS7-5618a
M-07-46	X09373	359	360.5	0.19	0.09	81	1.8	0.1	12	0.1	37	AS7-5618a
M-07-46	X09374	360.5	362.7	0.20	0.09	182	5.6	0.1	54	0.1	56	AS7-5618a
M-07-46	X09375	362.7	364.25	0.16	0.09	133	2.4	5	164	15	661	AS7-5618a
M-07-46	X09376	364.25	366.25	0.19	0.11	216	1.6	0.1	62	0.1	157	AS7-5618a
M-07-46	X09377	366.25	368	0.14	0.12	143	1.5	5	32	0.1	59	AS7-5618a
M-07-46	X09378	368	370	0.18	0.11	82	1.4	0.1	14	10	72	AS7-5618a
M-07-46	X09379	370	372	0.13	0.18	97	2.3	0.1	16	10	72	AS7-5618a
M-07-46	X09380	372	374	0.36	0.21	77	2.4	0.1	16	10	70	AS7-5618a
M-07-46	X09381	374	376	0.21	0.13	106	1.8	0.1	16	15	68	AS7-5618a
M-07-46	X09382	376	378	0.11	0.10	100	1.2	10	24	10	68	AS7-5623a
M-07-46	X09383	378	380	0.31	0.08	218	1	10	28	10	69	AS7-5623a
M-07-46	X09385	380	382	0.28	0.17	268	1.8	15	22	0.1	45	AS7-5623a
M-07-46	X09386	382	384	0.32	0.11	367	1.3	0.1	24	5	61	AS7-5623a
M-07-46	X09387	384	385.45	0.10	0.09	496	1.2	10	18	5	63	AS7-5623a
M-07-46	X09388	385.45	386.9	0.24	0.13	114	1.7	5	38	5	82	AS7-5623a
M-07-46	X09389	386.9	388.9	0.27	0.13	190	2.2	10	42	15	48	AS7-5623a
M-07-46	X09390	388.9	391	0.25	0.16	866	2	20	42	0.1	28	AS7-5623a
M-07-46	X09391	391	393	0.27	0.14	444	2	15	16	10	47	AS7-5623a
M-07-46	X09392	393	395	0.39	0.16	181	2.4	10	16	5	53	AS7-5623a
M-07-46	X09393	395	396.65	0.33	0.20	237	3.1	15	20	0.1	38	AS7-5623a
M-07-46	X09395	396.65	398	0.39	0.15	616	2.6	10	22	0.1	42	AS7-5623a
M-07-46	X09396	398	399.35	0.34	0.12	173	9.1	0.1	20	0.1	55	AS7-5623a
M-07-46	X09397	399.35	401	0.11	0.06	156	1.5	0.1	24	0.1	35	AS7-5623a
M-07-46	X09398	401	403	0.09	0.06	278	1.1	10	16	5	33	AS7-5623a
M-07-46	X09399	403	405	0.12	0.05	49	1.2	5	20	0.1	39	AS7-5623a
M-07-46	X09400	405	407	0.15	0.07	66	1.5	0.1	28	0.1	49	AS7-5623a
M-07-46	X09401	407	409.1	0.42	0.14	146	2.3	20	20	0.1	36	AS7-5623a
M-07-46	X09402	409.1	411	0.14	0.06	78	1	10	18	0.1	44	AS7-5623a
M-07-46	X09403	411	413	0.41	0.09	114	1.2	10	20	0.1	36	AS7-5623a
M-07-46	X09404	413	415	0.17	0.08	47	0.9	10	18	0.1	34	AS7-5623a
M-07-46	X09405	415	417	0.06	0.05	33	0.8	15	24	10	46	AS7-5623a
M-07-46	X09407	417	419	0.10	0.05	58	0.8	15	24	5	46	AS7-5623a
M-07-46	X09408	419	420.25	0.11	0.07	71	1.2	10	24	5	43	AS7-5623a
M-07-46	X09409	420.25	421.55	0.18	0.08	48	1	10	24	0.1	41	AS7-5623a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-46	X09410	421.55	423	0.17	0.08	79	1.1	15	38	10	41	AS7-5623a
M-07-46	X09411	423	424.3	0.13	0.05	33	0.9	20	16	0.1	32	AS7-5623a
M-07-47	G35908	9.75	12	0.72	0.11	94	1.3	0.1	46	5	90	AS7-5629a
M-07-47	G35909	12	14	0.58	0.09	155	1	0.1	36	10	83	AS7-5629a
M-07-47	G35910	14	16	0.64	0.11	264	1	10	44	0.1	74	AS7-5629a
M-07-47	G35911	16	18	0.55	0.08	81	0.7	0.1	32	10	113	AS7-5629a
M-07-47	G35912	18	20	0.56	0.09	97	1	0.1	32	5	123	AS7-5629a
M-07-47	G35913	20	22	0.60	0.06	119	1	5	50	10	141	AS7-5629a
M-07-47	G35914	22	24	0.43	0.07	58	0.9	0.1	46	0.1	131	AS7-5629a
M-07-47	G35915	24	26	0.54	0.08	50	1	10	44	10	158	AS7-5629a
M-07-47	G35916	26	28	0.40	0.09	77	1.4	15	56	5	126	AS7-5629a
M-07-47	G35917	28	30	0.50	0.15	111	1.8	10	88	20	140	AS7-5629a
M-07-47	G35918	30	32	0.72	0.11	82	1.2	0.1	102	10	155	AS7-5629a
M-07-47	G35919	32	34	0.63	0.09	104	1	0.1	50	10	268	AS7-5629a
M-07-47	G35920	34	36	0.51	0.07	101	0.7	0.1	46	10	149	AS7-5629a
M-07-47	G35921	36	38	0.65	0.12	101	1.3	0.1	48	10	267	AS7-5629a
M-07-47	G35922	38	40	1.01	0.16	82	2	0.1	58	0.1	151	AS7-5629a
M-07-47	G35923	40	42	0.54	0.13	69	1.6	0.1	84	10	259	AS7-5629a
M-07-47	G35924	42	44	0.70	0.13	78	1.3	0.1	62	10	218	AS7-5629a
M-07-47	G35926	44	46	1.03	0.16	87	2.1	5	270	0.1	515	AS7-5629a
M-07-47	G35927	46	48	0.88	0.17	76	1.9	0.1	68	10	99	AS7-5629a
M-07-47	G35928	48	50	0.93	0.16	111	1.5	0.1	44	15	86	AS7-5629a
M-07-47	G35929	50	52	0.69	0.14	70	1.2	0.1	36	20	78	AS7-5629a
M-07-47	G35930	52	54	0.44	0.16	68	1.3	0.1	46	15	102	AS7-5629a
M-07-47	G35931	54	56	0.73	0.16	92	1.5	0.1	84	15	163	AS7-5629a
M-07-47	G35933	56	58	0.63	0.11	75	1.3	10	40	10	111	AS7-5629a
M-07-47	G35934	58	60	0.96	0.17	70	1.5	10	32	15	110	AS7-5629a
M-07-47	G35935	60	61.59	0.89	0.27	42	1.8	0.1	36	10	116	AS7-5629a
M-07-47	G35936	61.59	63	0.28	0.17	76	1.6	5	74	5	109	AS7-5629a
M-07-47	G35937	63	65	0.44	0.22	63	1.9	0.1	50	0.1	93	AS7-5629a
M-07-47	G35938	65	67	0.73	0.12	126	1.1	0.1	38	10	83	AS7-5629a
M-07-47	G35939	67	69	0.71	0.11	113	1	0.1	40	15	89	AS7-5629a
M-07-47	G35940	69	71	0.88	0.20	68	2.1	0.1	44	20	80	AS7-5629a
M-07-47	G35941	71	73	0.97	0.16	38	1.9	0.1	62	10	134	AS7-5629a
M-07-47	G35942	73	75	0.92	0.13	67	1.6	10	34	10	98	AS7-5629a
M-07-47	G35943	75	77	1.14	0.13	56	1.1	10	48	15	98	AS7-5631a
M-07-47	G35944	77	79	0.66	0.10	26	1.2	0.1	86	5	80	AS7-5631a
M-07-47	G35945	79	81	0.49	0.08	51	0.8	0.1	40	10	106	AS7-5631a
M-07-47	G35946	81	83	0.59	0.09	46	1.1	10	42	15	75	AS7-5631a
M-07-47	G35948	83	85	0.79	0.07	33	0.7	5	36	20	95	AS7-5631a
M-07-47	G35949	85	87	0.43	0.19	45	1.9	0.1	74	0.1	97	AS7-5631a
M-07-47	G35950	87	89	0.74	0.16	54	2	0.1	90	15	184	AS7-5631a
M-07-47	G35951	89	91	0.29	0.05	46	2.4	0.1	38	0.1	41	AS7-5631a
M-07-47	G35952	91	93	0.25	0.01	42	13.7	15	28	5	14	AS7-5631a
M-07-47	G35953	93	95	0.60	0.03	49	6.8	50	66	50	278	AS7-5631a
M-07-47	G35954	95	97	0.13	0.02	32	0.7	0.1	32	0.1	17	AS7-5631a
M-07-47	G35956	97	99	0.33	0.10	28	1.6	0.1	42	0.1	84	AS7-5631a
M-07-47	G35957	99	101	0.13	0.14	37	1.2	0.1	54	0.1	103	AS7-5631a
M-07-47	G35958	101	103	0.19	0.10	28	1	0.1	22	0.1	30	AS7-5631a
M-07-47	G35959	103	105	0.36	0.12	42	3	0.1	40	0.1	29	AS7-5631a
M-07-47	G35960	105	107	0.18	0.15	44	1.6	0.1	128	10	40	AS7-5631a
M-07-47	G35961	107	109	0.27	0.13	46	1.3	0.1	92	5	273	AS7-5631a
M-07-47	G35962	109	111	1.73	0.23	22	6.5	0.1	96	0.1	539	AS7-5631a
M-07-47	G35963	111	113	0.46	0.11	31	1.8	0.1	90	0.1	556	AS7-5631a
M-07-47	G35964	113	115	0.67	0.15	34	2.5	0.1	48	5	324	AS7-5631a
M-07-47	G35965	115	117	0.17	0.08	35	1.5	0.1	92	0.1	193	AS7-5631a
M-07-47	G35966	117	119	0.08	0.14	25	1.8	0.1	84	0.1	402	AS7-5631a
M-07-47	G35967	119	121	0.07	0.10	29	1	0.1	34	0.1	33	AS7-5631a
M-07-47	G35968	121	123	0.38	0.10	59	1.1	0.1	28	0.1	89	AS7-5631a
M-07-47	G35969	123	125	0.37	0.11	48	1	15	42	15	67	AS7-5631a
M-07-47	G35970	125	127	0.57	0.14	33	1.7	20	38	15	71	AS7-5631a
M-07-47	G35972	127	129	0.36	0.16	34	1.5	0.1	36	0.1	32	AS7-5631a
M-07-47	G35973	129	131	0.66	0.15	23	1.1	0.1	34	0.1	63	AS7-5631a
M-07-47	G35974	131	133	0.48	0.09	26	0.8	0.1	22	0.1	68	AS7-5631a
M-07-47	G35975	133	135	0.13	0.12	25	0.6	0.1	36	0.1	179	AS7-5631a
M-07-47	G35976	135	137	0.34	0.15	23	0.9	0.1	32	0.1	35	AS7-5631a
M-07-47	G35977	137	139	0.89	0.12	21	1.6	0.1	20	0.1	50	AS7-5631a
M-07-47	G35978	139	141	0.18	0.12	35	1.8	0.1	18	0.1	45	AS7-5632a
M-07-47	G35979	141	143	0.17	0.17	25	3.4	0.1	24	0.1	52	AS7-5632a
M-07-47	G35980	143	145	0.44	0.12	17	1.4	0.1	40	0.1	53	AS7-5632a
M-07-47	G35981	145	147	0.21	0.16	20	2.5	0.1	30	0.1	35	AS7-5632a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-47	G35982	147	149	0.26	0.15	21	4.8	0.1	30	0.1	35	AS7-5632a
M-07-47	G35983	149	151	0.41	0.20	14	16.7	20	70	35	85	AS7-5632a
M-07-47	G35984	151	152.75	0.36	0.24	13	7	0.1	18	0.1	40	AS7-5632a
M-07-47	G35985	152.75	154	1.34	0.33	18	4.5	0.1	20	5	56	AS7-5632a
M-07-47	G35986	154	156	0.87	0.21	19	3.5	0.1	34	10	60	AS7-5632a
M-07-47	G35987	156	158	0.53	0.18	25	1.6	0.1	26	0.1	64	AS7-5632a
M-07-47	G35988	158	160	0.27	0.11	18	1.3	0.1	34	15	42	AS7-5632a
M-07-47	G35990	160	162	0.47	0.34	13	3.4	0.1	34	10	67	AS7-5632a
M-07-47	G35991	162	164	0.56	0.21	12	1.9	0.1	32	5	61	AS7-5632a
M-07-47	G35992	164	166	0.28	0.28	10	2.6	0.1	48	5	79	AS7-5632a
M-07-47	G35993	166	168.1	1.18	0.41	50	3.8	0.1	30	10	117	AS7-5632a
M-07-47	G35994	168.1	170	0.34	0.21	15	5.6	0.1	138	20	549	AS7-5632a
M-07-47	G35995	170	172	0.51	0.16	12	11.7	25	42	75	161	AS7-5632a
M-07-47	G35996	172	174	0.14	0.01	43	1	0.1	8	10	11	AS7-5632a
M-07-47	G35998	174	176	0.10	0.07	20	1.9	0.1	18	10	25	AS7-5632a
M-07-47	G35999	176	178	0.27	0.10	22	2.3	0.1	20	25	22	AS7-5632a
M-07-47	G36000	178	180	0.13	0.14	14	1.6	0.1	24	10	36	AS7-5632a
M-07-47	X05001	180	182	0.14	0.17	17	2.4	0.1	28	10	25	AS7-5632a
M-07-47	X05002	182	184	0.10	0.01	123	0.3	0.1	14	0.1	165	AS7-5632a
M-07-47	X05003	184	186	0.08	0.02	73	0.3	0.1	14	0.1	2	AS7-5632a
M-07-47	X05004	186	188	0.09	0.15	15	1.7	0.1	14	0.1	16	AS7-5632a
M-07-47	X05005	188	190	0.10	0.07	31	1.7	0.1	22	0.1	7	AS7-5632a
M-07-47	X05006	190	192	0.03	0.01	48	0.4	0.1	14	0.1	40	AS7-5632a
M-07-47	X05007	192	194	0.12	0.19	15	3.1	20	24	15	17	AS7-5632a
M-07-47	X05008	194	196	0.12	0.16	12	2.8	10	16	30	17	AS7-5632a
M-07-47	X05009	196	198	0.09	0.14	18	3.1	20	16	20	38	AS7-5632a
M-07-47	X05010	198	200	0.11	0.27	11	4.4	25	20	40	47	AS7-5632a
M-07-47	X05011	200	202	0.14	0.21	9	2	10	34	10	73	AS7-5632a
M-07-47	X05012	202	204	0.16	0.40	18	3.7	0.1	44	0.1	132	AS7-5632a
M-07-47	X05013	204	206	0.26	0.36	7	2.6	0.1	30	0.1	92	AS7-5634a
M-07-47	X05014	206	208	0.25	0.42	12	2.4	0.1	32	0.1	57	AS7-5634a
M-07-47	X05015	208	210	0.69	0.37	11	2.8	0.1	26	0.1	32	AS7-5634a
M-07-47	X05016	210	212	0.73	0.42	9	6.3	15	30	40	42	AS7-5634a
M-07-47	X05017	212	214	0.46	0.31	13	2.4	0.1	18	0.1	16	AS7-5634a
M-07-47	X05018	214	216	0.50	0.21	7	1.4	0.1	20	0.1	31	AS7-5634a
M-07-47	X05019	216	218	0.41	0.20	9	1.6	0.1	30	0.1	94	AS7-5634a
M-07-47	X05020	218	220	0.27	0.21	10	2.2	15	34	0.1	62	AS7-5634a
M-07-47	X05021	220	222	0.76	0.11	13	1.1	0.1	14	0.1	26	AS7-5634a
M-07-47	X05023	222	224	0.41	0.09	9	1	0.1	12	0.1	27	AS7-5634a
M-07-47	X05024	224	226	0.45	0.25	13	2	0.1	28	0.1	42	AS7-5634a
M-07-47	X05025	226	228	0.59	0.30	10	2.4	0.1	24	0.1	27	AS7-5634a
M-07-47	X05027	228	230	0.15	0.19	12	2.7	5	34	10	33	AS7-5634a
M-07-47	X05028	230	232	0.24	0.22	34	2	0.1	22	0.1	14	AS7-5634a
M-07-47	X05029	232	234	0.26	0.20	14	2.4	0.1	38	10	42	AS7-5634a
M-07-47	X05030	234	236	0.48	0.38	10	2.2	0.1	26	0.1	29	AS7-5634a
M-07-47	X05031	236	237.5	0.25	0.34	14	4.3	0.1	54	0.1	57	AS7-5634a
M-07-47	X05032	237.5	239	0.57	0.32	15	7.3	0.1	140	5	89	AS7-5634a
M-07-47	X05033	239	241	1.00	0.26	9	2.6	0.1	22	0.1	44	AS7-5634a
M-07-47	X05034	241	243	0.72	0.25	11	2.3	0.1	30	0.1	51	AS7-5634a
M-07-47	X05035	243	245	0.76	0.44	7	3.2	0.1	32	0.1	35	AS7-5634a
M-07-47	X05036	245	247	0.67	0.18	10	1.5	0.1	28	0.1	36	AS7-5634a
M-07-47	X05037	247	249	0.96	0.24	11	2.1	0.1	46	0.1	39	AS7-5634a
M-07-47	X05038	249	251	0.91	0.23	12	1.8	0.1	30	0.1	43	AS7-5634a
M-07-47	X05039	251	253	0.38	0.23	15	2.1	0.1	28	0.1	31	AS7-5634a
M-07-47	X05041	253	255	0.43	0.32	10	1.9	0.1	38	0.1	47	AS7-5634a
M-07-47	X05042	255	257	0.21	0.20	7	1.4	0.1	48	0.1	49	AS7-5634a
M-07-47	X05043	257	259	0.77	0.24	11	1.8	0.1	32	0.1	58	AS7-5634a
M-07-47	X05044	259	261	0.52	0.23	9	1.6	0.1	30	0.1	34	AS7-5634a
M-07-47	X05045	261	263	0.75	0.29	37	2.1	0.1	20	0.1	25	AS7-5634a
M-07-47	X05046	263	265	0.43	0.50	9	5.9	15	52	20	103	AS7-5634a
M-07-47	X05047	265	267	0.79	0.23	12	2.7	0.1	26	0.1	53	AS7-5634a
M-07-47	X05048	267	269	0.37	0.24	7	4.2	0.1	36	0.1	67	AS7-5635a
M-07-47	X05049	269	271	0.41	0.57	15	6.9	0.1	48	0.1	119	AS7-5635a
M-07-47	X05050	271	273	0.56	0.16	11	15.3	5	52	5	70	AS7-5635a
M-07-47	X05051	273	275	0.80	0.21	8	7.6	0.1	34	0.1	74	AS7-5635a
M-07-47	X05052	275	277	0.45	0.27	16	4.2	0.1	62	0.1	66	AS7-5635a
M-07-47	X05053	277	279	0.84	0.14	12	1.5	0.1	14	0.1	77	AS7-5635a
M-07-47	X05054	279	281	0.70	0.20	11	2.2	0.1	16	0.1	64	AS7-5635a
M-07-47	X05055	281	283	0.48	0.17	10	2.1	0.1	38	0.1	73	AS7-5635a
M-07-47	X05056	283	285	0.50	0.14	12	2.1	0.1	18	0.1	89	AS7-5635a
M-07-47	X05057	285	287	1.01	0.24	9	2.9	0.1	20	0.1	72	AS7-5635a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-47	X05058	287	289	0.84	0.33	24	2.8	0.1	46	0.1	60	AS7-5635a
M-07-47	X05059	289	291	0.57	0.32	9	2.2	0.1	76	0.1	113	AS7-5635a
M-07-47	X05060	291	293	0.57	0.26	11	1.6	0.1	62	0.1	122	AS7-5635a
M-07-47	X05062	293	295	0.73	0.29	10	2.9	0.1	42	0.1	242	AS7-5635a
M-07-47	X05063	295	297	0.56	0.37	15	2.2	0.1	108	0.1	190	AS7-5635a
M-07-47	X05064	297	299	0.51	0.27	6	0.01	0.1	48	0.1	53	AS7-5635a
M-07-47	X05065	299	301	0.53	0.25	11	2.5	0.1	74	0.1	151	AS7-5635a
M-07-47	X05066	301	303	0.60	0.31	11	3	0.1	48	0.1	82	AS7-5635a
M-07-47	X05067	303	305	0.66	0.34	10	2.6	0.1	50	0.1	50	AS7-5635a
M-07-47	X05068	305	307	0.31	0.19	9	2.3	0.1	90	0.1	189	AS7-5635a
M-07-47	X05069	307	309	0.42	0.17	13	1.7	0.1	38	0.1	101	AS7-5635a
M-07-47	X05070	309	311	0.79	0.19	12	1.9	0.1	30	0.1	82	AS7-5635a
M-07-47	X05071	311	313	0.54	0.22	8	2.8	0.1	98	0.1	178	AS7-5635a
M-07-47	X05072	313	315	0.41	0.26	11	2.2	0.1	32	0.1	45	AS7-5635a
M-07-47	X05074	315	317	0.37	0.27	27	2.6	0.1	56	0.1	935	AS7-5635a
M-07-47	X05075	317	319	0.59	0.18	12	1.9	0.1	22	0.1	51	AS7-5635a
M-07-47	X05076	319	321	0.73	0.21	10	4.2	0.1	40	0.1	104	AS7-5635a
M-07-47	X05077	321	323	0.46	0.26	15	4.9	10	48	0.1	50	AS7-5635a
M-07-47	X05078	323	325	0.46	0.31	15	3	0.1	62	0.1	56	AS7-5635a
M-07-47	X05079	325	327	0.46	0.37	28	4	10	78	0.1	80	AS7-5635a
M-07-47	X05080	327	329	0.44	0.26	11	3.4	0.1	122	0.1	149	AS7-5635a
M-07-47	X05081	329	331	0.56	0.21	11	2.2	0.1	20	0.1	61	AS7-5635a
M-07-47	X05082	331	333	0.58	0.33	10	3.2	0.1	24	0.1	32	AS7-5635a
M-07-47	X05083	333	335	0.71	0.34	9	3	10	46	0.1	72	AS7 - 5638a
M-07-47	X05084	335	337	1.18	0.39	5	3.6	10	50	0.1	59	AS7 - 5638a
M-07-47	X05085	337	339	0.87	0.24	10	2.2	10	20	0.1	67	AS7 - 5638a
M-07-47	X05086	339	341	1.36	0.34	9	3.4	10	20	0.1	39	AS7 - 5638a
M-07-47	X05087	341	343	1.27	0.47	8	6.2	15	60	0.1	93	AS7 - 5638a
M-07-47	X05088	343	345	0.60	0.17	9	3	25	28	5	86	AS7 - 5638a
M-07-47	X05089	345	347	0.56	0.19	67	4.9	30	86	15	220	AS7 - 5638a
M-07-47	X05090	347	349	0.42	0.40	6	4.9	70	48	85	107	AS7 - 5638a
M-07-47	X05091	349	351	0.38	0.19	13	3.4	25	30	5	109	AS7 - 5638a
M-07-47	X05092	351	353	0.67	0.20	5	5.3	15	40	0.1	104	AS7 - 5638a
M-07-47	X05093	353	355	0.64	0.22	11	5.1	20	22	0.1	74	AS7 - 5638a
M-07-47	X05094	355	357	0.74	0.14	7	5.2	45	38	5	70	AS7 - 5638a
M-07-47	X05095	357	359	0.60	0.27	10	8.5	35	68	5	122	AS7 - 5638a
M-07-47	X05097	359	361	0.45	0.29	6	10.9	20	110	0.1	324	AS7 - 5638a
M-07-47	X05098	361	363	0.74	0.31	10	8.5	25	54	0.1	152	AS7 - 5638a
M-07-47	X05099	363	365	0.64	0.20	5	2.1	15	34	0.1	183	AS7 - 5638a
M-07-47	X05151	365	367	0.42	0.47	9	5.4	20	132	0.1	301	AS7 - 5638a
M-07-47	X05152	367	369	0.51	0.29	8	3.2	15	26	0.1	91	AS7 - 5638a
M-07-47	X05153	369	371	0.55	0.30	10	3.1	20	42	0.1	122	AS7 - 5638a
M-07-47	X05154	371	373	0.60	0.23	10	2.7	15	54	0.1	96	AS7 - 5638a
M-07-47	X05155	373	375	0.55	0.21	13	2.6	15	36	0.1	139	AS7 - 5638a
M-07-47	X05156	375	377	0.56	0.31	5	4.2	20	36	0.1	196	AS7 - 5638a
M-07-47	X05157	377	379	1.23	0.46	8	5.6	15	54	0.1	132	AS7 - 5638a
M-07-47	X05158	379	381	1.09	0.34	7	3.7	15	34	0.1	131	AS7 - 5638a
M-07-47	X05159	381	383	0.75	0.18	11	2.2	20	24	0.1	154	AS7 - 5638a
M-07-47	X05160	383	385	0.75	0.18	7	2.2	15	42	0.1	195	AS7 - 5638a
M-07-47	X05161	385	387	1.01	0.20	10	2.7	15	40	0.1	146	AS7 - 5638a
M-07-47	X05162	387	389	0.78	0.27	9	5	15	118	0.1	268	AS7 - 5638a
M-07-47	X05163	389	391	0.55	0.19	12	5.7	20	92	0.1	395	AS7 - 5638a
M-07-47	X05164	391	393	0.83	0.29	8	4.7	25	60	0.1	170	AS7 - 5638a
M-07-47	X05165	393	395	0.69	0.28	11	6.4	45	74	10	162	AS7 - 5638a
M-07-47	X05167	395	397	0.59	0.19	16	2.3	15	26	0.1	103	AS7 - 5638a
M-07-47	X05168	397	399	1.02	0.40	7	5	10	70	0.1	80	AS7-5646a
M-07-47	X05169	399	401	0.60	0.19	7	2.6	15	52	0.1	110	AS7-5646a
M-07-47	X05170	401	403	0.70	0.18	9	2.3	10	22	0.1	80	AS7-5646a
M-07-47	X05171	403	405	0.98	0.33	8	4.7	15	50	0.1	141	AS7-5646a
M-07-47	X05172	405	407	0.72	0.29	9	3.5	10	56	0.1	65	AS7-5646a
M-07-47	X05173	407	410.15	1.07	0.36	9	4.1	10	24	0.1	87	AS7-5646a
M-07-47	X05174	411	413	0.69	0.21	11	2.6	10	50	0.1	96	AS7-5646a
M-07-47	X05175	413	415	0.86	0.23	14	2.1	10	52	0.1	82	AS7-5646a
M-07-47	X05176	415	417	0.61	0.27	7	2.4	10	66	0.1	89	AS7-5646a
M-07-47	X05177	417	419	0.64	0.18	10	1.9	10	32	0.1	74	AS7-5646a
M-07-47	X05178	419	421	0.94	0.26	11	2.4	10	24	0.1	66	AS7-5646a
M-07-47	X05179	421	423	0.54	0.20	12	2.5	15	28	0.1	65	AS7-5646a
M-07-47	X05180	423	425	0.88	0.20	8	2.1	5	16	0.1	36	AS7-5646a
M-07-47	X05182	425	427	0.63	0.24	16	2.7	5	40	0.1	36	AS7-5646a
M-07-47	X05183	427	428.6	0.88	0.27	8	3.2	5	52	0.1	64	AS7-5646a
M-07-47	X05184	428.6	430.3	1.02	0.17	11	1.6	5	18	0.1	62	AS7-5646a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-47	X05185	430.3	432	2.16	0.53	5	5.4	5	40	0.1	20	AS7-5646a
M-07-47	X05186	432	434	1.52	0.52	8	36.9	25	120	25	216	AS7-5646a
M-07-47	X05187	434	436	0.63	0.32	7	18	10	36	5	105	AS7-5646a
M-07-47	X05188	436	438	1.30	0.33	5	4.2	5	24	0.1	37	AS7-5646a
M-07-47	X05189	438	440.2	0.90	0.31	5	10.7	20	24	0.1	46	AS7-5646a
M-07-47	X05190	440.2	442.55	0.83	0.39	11	152	295	196	430	412	AS7-5646a
M-07-48	X09412	6.4	8	1.01	0.20	20	1.6	20	38	10	99	AS7-5626a
M-07-48	X09413	8	10	1.18	0.49	14	2.5	10	32	5	58	AS7-5626a
M-07-48	X09414	10	12	0.58	0.40	10	2.4	30	30	10	33	AS7-5626a
M-07-48	X09415	12	14	0.54	0.30	15	3.5	175	26	25	70	AS7-5626a
M-07-48	X09416	14	16	0.50	0.44	12	2.8	355	32	20	123	AS7-5626a
M-07-48	X09417	16	18	0.63	0.39	14	1.7	15	24	0.1	23	AS7-5626a
M-07-48	X09418	18	20	0.84	0.45	11	3.4	0.1	40	0.1	48	AS7-5626a
M-07-48	X09419	20	22	0.74	0.25	17	1.8	0.1	38	0.1	62	AS7-5626a
M-07-48	X09421	22	24	1.16	0.38	19	2	0.1	36	0.1	52	AS7-5626a
M-07-48	X09422	24	26	0.97	0.32	17	1.4	0.1	32	15	106	AS7-5626a
M-07-48	X09423	26	28	1.03	0.50	15	1.8	0.1	36	0.1	53	AS7-5626a
M-07-48	X09424	28	29.55	1.25	0.47	12	1.6	0.1	34	0.1	48	AS7-5626a
M-07-48	X09425	29.55	31	1.39	0.31	16	1.3	0.1	36	15	79	AS7-5626a
M-07-48	X09426	31	33	1.23	0.32	14	1	0.1	62	0.1	82	AS7-5626a
M-07-48	X09427	33	34.25	0.79	0.28	19	1.1	0.1	48	10	59	AS7-5626a
M-07-48	X09428	34.25	35.65	0.75	0.19	17	0.8	0.1	60	15	87	AS7-5626a
M-07-48	X09429	35.65	37	0.74	0.43	20	2.8	0.1	190	0.1	492	AS7-5626a
M-07-48	X09430	37	39	0.35	0.39	11	2	0.1	124	0.1	58	AS7-5626a
M-07-48	X09432	39	41	1.07	0.42	14	2.5	0.1	84	0.1	93	AS7-5626a
M-07-48	X09433	41	41.85	0.80	0.49	12	2.7	15	114	10	134	AS7-5626a
M-07-48	X09434	41.85	43	1.21	0.26	17	1.3	0.1	54	0.1	70	AS7-5626a
M-07-48	X09435	43	45	1.02	0.25	15	1.4	0.1	72	0.1	115	AS7-5626a
M-07-48	X09437	45	47	0.88	0.29	18	1.7	0.1	88	0.1	283	AS7-5626a
M-07-48	X09438	47	49	0.82	0.17	17	1	0.1	50	0.1	136	AS7-5626a
M-07-48	X09439	49	51	1.25	0.35	18	2.8	0.1	98	0.1	88	AS7-5626a
M-07-48	X09440	51	53	1.08	0.26	20	1.8	0.1	40	5	96	AS7-5626a
M-07-48	X09441	53	54.65	1.11	0.31	19	1.5	0.1	46	0.1	123	AS7-5626a
M-07-48	X09442	54.65	56	1.05	0.27	17	1.3	0.1	40	0.1	47	AS7-5626a
M-07-48	X09443	56	57.8	0.99	0.26	18	1.5	0.1	46	0.1	117	AS7-5626a
M-07-48	X09444	57.8	58.8	0.74	0.17	23	1.2	0.1	36	10	86	AS7-5626a
M-07-48	X09445	59.9	62	1.32	0.31	18	1.4	0.1	24	0.1	32	AS7-5626a
M-07-48	X09446	62	64	1.17	0.32	22	1.6	15	30	0.1	39	AS7-5626a
M-07-48	X09447	64	66	0.80	0.20	10	0.8	0.1	26	0.1	72	AS7-5627a
M-07-48	X09448	66	68	0.99	0.24	11	1.2	0.1	16	0.1	46	AS7-5627a
M-07-48	X09449	68	70	1.09	0.19	14	1.3	0.1	24	0.1	61	AS7-5627a
M-07-48	X09450	70	72	0.98	0.21	10	1.3	0.1	28	0.1	28	AS7-5627a
M-07-48	X09451	72	74	1.02	0.22	16	1.1	0.1	30	0.1	54	AS7-5627a
M-07-48	X09452	74	76	1.31	0.26	13	1.5	10	26	0.1	78	AS7-5627a
M-07-48	X09453	76	78	1.23	0.26	14	1	0.1	28	0.1	43	AS7-5627a
M-07-48	X09454	78	80	1.03	0.17	12	1.1	5	18	5	19	AS7-5627a
M-07-48	X09456	80	81.85	0.81	0.16	8	0.9	20	28	0.1	21	AS7-5627a
M-07-48	X09457	81.85	82.9	0.29	0.00	13	0.01	30	40	25	174	AS7-5627a
M-07-48	X09458	82.9	84	1.03	0.25	12	2.4	50	28	10	41	AS7-5627a
M-07-48	X09459	84	86	0.99	0.25	12	1.6	0.1	24	10	43	AS7-5627a
M-07-48	X09460	86	88	0.44	0.33	13	2.1	0.1	12	0.1	28	AS7-5627a
M-07-48	X09461	88	90	1.63	0.25	8	2.2	15	14	0.1	102	AS7-5627a
M-07-48	X09462	90	92	1.73	0.32	14	2.5	25	20	0.1	20	AS7-5627a
M-07-48	X09463	92	94	0.75	0.26	11	1.9	30	14	10	20	AS7-5627a
M-07-48	X09464	94	96	0.35	0.28	15	1.8	25	32	0.1	18	AS7-5627a
M-07-48	X09465	96	98	0.50	0.34	10	1.9	5	20	0.1	30	AS7-5627a
M-07-48	X09466	98	100	0.71	0.27	12	2.1	0.1	16	0.1	29	AS7-5627a
M-07-48	X09467	100	102	0.60	0.26	13	2.3	0.1	96	0.1	231	AS7-5627a
M-07-48	X09468	102	104	0.74	0.23	17	2	20	20	0.1	65	AS7-5627a
M-07-48	X09469	104	106	1.55	0.22	11	2	110	30	10	40	AS7-5627a
M-07-48	X09470	106	108	0.59	0.22	15	1.3	0.1	24	0.1	10	AS7-5627a
M-07-48	X09471	108	110	0.70	0.21	32	1.3	0.1	10	0.1	33	AS7-5627a
M-07-48	X09472	110	112	0.67	0.33	12	1.9	0.1	22	0.1	14	AS7-5627a
M-07-48	X09474	112	114	0.57	0.30	7	1.4	0.1	16	0.1	14	AS7-5627a
M-07-48	X09475	114	116	0.95	0.24	14	1.6	0.1	24	10	29	AS7-5627a
M-07-48	X09476	116	118	0.71	0.23	9	1.8	0.1	12	0.1	12	AS7-5627a
M-07-48	X09477	118	120	0.42	0.21	17	1.4	0.1	16	0.1	23	AS7-5627a
M-07-48	X09478	120	122	0.41	0.29	13	1.6	0.1	20	0.1	17	AS7-5627a
M-07-48	X09479	122	124	0.51	0.19	9	1.8	20	16	0.1	30	AS7-5627a
M-07-48	X09480	124	124.9	0.38	0.16	16	3.2	105	90	20	276	AS7-5627a
M-07-48	X09481	125.8	128	0.56	0.23	19	2.5	20	28	10	78	AS7-5627a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-48	X09482	128	130	1.05	0.24	13	1.6	15	26	0.1	31	AS7-5628a
M-07-48	X09483	130	132	0.34	0.21	23	1.3	0.1	36	0.1	117	AS7-5628a
M-07-48	X09484	132	134	0.38	0.17	29	1.1	0.1	24	0.1	40	AS7-5628a
M-07-48	X09485	134	136	0.53	0.15	41	0.9	0.1	24	0.1	30	AS7-5628a
M-07-48	X09486	136	138	0.46	0.20	41	0.9	0.1	14	0.1	23	AS7-5628a
M-07-48	X09487	138	140	0.67	0.18	36	0.9	0.1	38	0.1	59	AS7-5628a
M-07-48	X09488	140	142	0.76	0.18	23	2.7	85	174	60	512	AS7-5628a
M-07-48	X09489	142	144	0.77	0.18	26	1.8	10	48	15	47	AS7-5628a
M-07-48	X09490	144	146	0.96	0.17	33	1.1	0.1	146	0.1	167	AS7-5628a
M-07-48	X09491	146	148	0.73	0.20	144	1.3	0.1	46	0.1	72	AS7-5628a
M-07-48	X09493	148	150.1	0.36	0.15	36	1.3	20	32	0.1	64	AS7-5628a
M-07-48	X09494	150.85	152	0.72	0.18	17	1.3	10	54	0.1	122	AS7-5628a
M-07-48	X09495	152	154	0.45	0.14	33	1.2	0.1	30	0.1	44	AS7-5628a
M-07-48	X09496	154	156	0.55	0.20	35	1.3	0.1	22	0.1	36	AS7-5628a
M-07-48	X09497	156	158	1.10	0.21	39	1.4	0.1	16	0.1	7	AS7-5628a
M-07-48	X09498	158	160	0.54	0.15	18	1.2	0.1	24	0.1	25	AS7-5628a
M-07-48	X09499	160	162	0.27	0.15	18	1.3	10	16	0.1	29	AS7-5628a
M-07-48	X09501	162	164	0.20	0.08	27	2	55	18	30	156	AS7-5628a
M-07-48	X09502	164	166	0.47	0.19	26	4.4	15	42	20	35	AS7-5628a
M-07-48	X09503	166	168	0.34	0.16	39	1.7	20	28	10	17	AS7-5628a
M-07-48	X09504	168	170	0.74	0.23	52	2.4	30	24	10	32	AS7-5628a
M-07-48	X09505	170	172	0.52	0.16	39	7.2	145	84	80	155	AS7-5628a
M-07-48	X09506	172	174	0.86	0.19	44	2.3	25	78	10	91	AS7-5628a
M-07-48	X09507	174	176	0.64	0.16	34	1.6	0.1	40	0.1	41	AS7-5628a
M-07-48	X09508	176	178	1.03	0.18	88	2.2	0.1	154	0.1	345	AS7-5628a
M-07-48	X09509	178	180	0.61	0.14	45	1.3	0.1	28	0.1	37	AS7-5628a
M-07-48	X09510	180	182	0.71	0.14	34	1	0.1	26	0.1	50	AS7-5628a
M-07-48	X09512	182	184	0.99	0.11	63	0.8	0.1	32	0.1	21	AS7-5628a
M-07-48	X09513	184	186	0.70	0.21	54	1.9	0.1	18	0.1	16	AS7-5628a
M-07-48	X09514	186	188	0.47	0.15	55	1	0.1	24	0.1	22	AS7-5628a
M-07-48	X09515	188	190	0.60	0.12	45	1.4	0.1	56	0.1	78	AS7-5628a
M-07-48	X09516	190	192	0.55	0.11	41	1	0.1	102	0.1	69	AS7-5628a
M-07-48	X09517	192	194	0.57	0.15	59	1.8	0.1	82	0.1	74	AS7-5633a
M-07-48	X09518	194	196	0.39	0.12	37	1.5	5	62	0.1	23	AS7-5633a
M-07-48	X09519	196	198	0.67	0.12	69	1.9	0.1	30	0.1	83	AS7-5633a
M-07-48	X09520	198	200	0.52	0.12	51	1.8	5	30	0.1	22	AS7-5633a
M-07-48	X09521	200	202	0.48	0.14	65	3	15	48	0.1	29	AS7-5633a
M-07-48	X09523	202	204	0.48	0.15	140	6.1	95	134	25	112	AS7-5633a
M-07-48	X09524	204	206	0.45	0.15	91	7.3	50	40	15	39	AS7-5633a
M-07-48	X09525	206	208	0.45	0.13	75	4.8	0.1	30	0.1	35	AS7-5633a
M-07-48	X09526	208	209.8	0.51	0.14	81	6.9	0.1	52	0.1	25	AS7-5633a
M-07-48	X09527	209.8	211	0.73	0.18	63	6.5	0.1	22	0.1	53	AS7-5633a
M-07-48	X09528	211	213	0.85	0.19	114	2.8	0.1	18	0.1	31	AS7-5633a
M-07-48	X09529	213	215	0.73	0.22	163	3	0.1	20	0.1	28	AS7-5633a
M-07-48	X09530	215	217	0.63	0.24	78	2.7	0.1	24	0.1	14	AS7-5633a
M-07-48	X09531	217	219	0.53	0.16	142	3.1	0.1	114	0.1	80	AS7-5633a
M-07-48	X09532	219	221	0.97	0.24	130	5.4	0.1	22	0.1	26	AS7-5633a
M-07-48	X09533	221	223	0.97	0.35	155	7.9	10	20	5	18	AS7-5633a
M-07-48	X09535	223	225	1.09	0.22	115	3.2	0.1	16	0.1	29	AS7-5633a
M-07-48	X09536	225	227	1.41	0.31	108	2.6	0.1	26	0.1	33	AS7-5633a
M-07-48	X09537	227	229	1.08	0.23	82	1.9	0.1	38	0.1	29	AS7-5633a
M-07-48	X09538	229	231	1.09	0.26	132	2.3	0.1	34	0.1	30	AS7-5633a
M-07-48	X09539	231	233	1.29	0.26	94	1.8	0.1	18	0.1	24	AS7-5633a
M-07-48	X09540	233	235	1.09	0.20	103	2.3	0.1	26	0.1	51	AS7-5633a
M-07-48	X09541	235	237	0.89	0.21	68	3.3	0.1	22	0.1	18	AS7-5633a
M-07-48	X09542	237	239	0.98	0.19	133	2	0.1	22	0.1	30	AS7-5633a
M-07-48	X09543	239	241	0.91	0.24	82	6.8	0.1	18	0.1	29	AS7-5633a
M-07-48	X09544	241	243	0.65	0.22	108	8.2	5	24	0.1	22	AS7-5633a
M-07-48	X09546	243	245	0.87	0.22	100	7.6	0.1	298	0.1	1579	AS7-5633a
M-07-48	X09547	245	247	0.87	0.23	234	4.4	0.1	18	0.1	41	AS7-5633a
M-07-48	X09548	247	249	0.69	0.22	431	9.4	60	190	25	561	AS7-5633a
M-07-48	X09549	249	251	0.64	0.20	163	12.6	50	294	25	1286	AS7-5633a
M-07-48	X09550	251	253	0.60	0.19	99	9.2	0.1	462	0.1	1561	AS7-5633a
M-07-48	X09551	253	255	1.01	0.18	79	3.2	0.1	22	0.1	65	AS7-5633a
M-07-48	X09552	255	257	0.94	0.19	86	3.9	15	22	0.1	52	AS7-5636a
M-07-48	X09553	257	259	1.11	0.23	110	4.5	15	26	0.1	45	AS7-5636a
M-07-48	X09554	259	261	0.72	0.21	126	3.6	15	16	0.1	34	AS7-5636a
M-07-48	X09555	261	263	0.80	0.18	55	3.1	20	14	0.1	62	AS7-5636a
M-07-48	X09556	263	265	0.76	0.17	46	2.7	10	6	0.1	44	AS7-5636a
M-07-48	X09557	265	267	0.95	0.18	68	3.6	20	6	0.1	60	AS7-5636a
M-07-48	X09558	267	269	0.99	0.25	125	5.3	20	10	0.1	45	AS7-5636a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-48	X09559	269	271	0.82	0.25	73	10.8	40	26	0.1	59	AS7-5636a
M-07-48	X09560	271	273	0.92	0.24	53	7.8	15	16	0.1	44	AS7-5636a
M-07-48	X09561	273	275	1.08	0.24	65	3.2	15	10	0.1	70	AS7-5636a
M-07-48	X09562	275	277	0.89	0.14	36	2	25	6	0.1	78	AS7-5636a
M-07-48	X09563	277	279	0.80	0.14	85	2.4	25	204	0.1	144	AS7-5636a
M-07-48	X09565	279	281	0.59	0.13	39	2.8	25	40	0.1	64	AS7-5636a
M-07-48	X09566	281	283	0.84	0.20	104	3.8	20	14	0.1	61	AS7-5636a
M-07-48	X09567	283	285	0.73	0.22	61	5.1	25	28	0.1	48	AS7-5636a
M-07-48	X09568	285	287	0.46	0.15	63	3.4	35	14	0.1	44	AS7-5636a
M-07-48	X09569	287	289	0.57	0.19	48	4.3	30	42	0.1	82	AS7-5636a
M-07-48	X09570	289	291	0.48	0.11	68	2	25	24	0.1	145	AS7-5636a
M-07-48	X09571	291	293	0.47	0.15	34	2.9	20	56	0.1	95	AS7-5636a
M-07-48	X09573	293	295	0.29	0.20	61	4.8	20	18	0.1	50	AS7-5636a
M-07-48	X09574	295	297	1.06	0.27	231	4.9	20	14	0.1	108	AS7-5636a
M-07-48	X09575	297	299	0.43	0.13	60	2.6	20	24	0.1	111	AS7-5636a
M-07-48	X09576	299	300.5	0.66	0.18	34	8.8	20	476	0.1	194	AS7-5636a
M-07-48	X09577	300.5	301.7	0.59	0.27	64	5.7	20	54	0.1	54	AS7-5636a
M-07-48	X09578	301.7	303	0.40	0.14	61	4.8	25	144	0.1	41	AS7-5636a
M-07-48	X09579	303	305	0.62	0.16	57	3.1	15	12	0.1	75	AS7-5636a
M-07-48	X09580	305	307	0.53	0.14	70	1.4	15	8	0.1	59	AS7-5636a
M-07-48	X09581	307	309	0.93	0.21	81	2.4	15	14	0.1	54	AS7-5636a
M-07-48	X09582	309	311	0.60	0.14	56	1.5	15	10	0.1	63	AS7-5636a
M-07-48	X09583	311	313	0.64	0.19	64	2.2	25	16	0.1	67	AS7-5636a
M-07-48	X09585	313	315	0.42	0.12	90	1.1	15	10	0.1	77	AS7-5636a
M-07-48	X09586	315	317	0.65	0.16	66	0.01	20	22	0.1	67	AS7-5636a
M-07-48	X09587	317	319	0.68	0.12	470	2.6	15	16	0.1	85	AS7 - 5637a
M-07-48	X09588	319	321	0.54	0.13	56	1.2	20	50	0.1	96	AS7 - 5637a
M-07-48	X09589	321	323	0.70	0.17	72	1.3	15	8	0.1	71	AS7 - 5637a
M-07-48	X09590	323	325	0.68	0.15	79	1.9	15	10	0.1	55	AS7 - 5637a
M-07-48	X09591	325	327	0.83	0.24	91	2.1	15	10	0.1	47	AS7 - 5637a
M-07-48	X09592	327	329	0.65	0.15	61	1.4	15	8	0.1	67	AS7 - 5637a
M-07-48	X09593	329	331	0.55	0.11	71	2.1	20	10	0.1	64	AS7 - 5637a
M-07-48	X09594	331	333	0.37	0.16	62	4.7	30	90	0.1	34	AS7 - 5637a
M-07-48	X09595	333	335	0.33	0.14	79	4.3	20	116	0.1	35	AS7 - 5637a
M-07-48	X09596	335	337	0.68	0.19	254	6.6	40	102	5	125	AS7 - 5637a
M-07-48	X09598	337	339	0.56	0.14	61	4.2	20	20	0.1	51	AS7 - 5637a
M-07-48	X09599	339	341	0.69	0.14	92	4.3	20	12	0.1	41	AS7 - 5637a
M-07-48	X09600	341	342.4	0.58	0.14	65	2.6	15	8	0.1	58	AS7 - 5637a
M-07-48	X09601	342.4	343.8	0.11	0.03	8	0.6	40	2	0.1	93	AS7 - 5637a
M-07-48	X09602	343.8	345	0.36	0.09	69	3.3	35	40	0.1	47	AS7 - 5637a
M-07-48	X09603	345	347	0.36	0.08	32	2.2	25	12	0.1	107	AS7 - 5637a
M-07-48	X09604	347	349	0.52	0.13	54	2.1	20	8	0.1	68	AS7 - 5637a
M-07-48	X09605	349	351	0.37	0.09	46	1.5	15	8	0.1	82	AS7 - 5637a
M-07-48	X09606	351	353	0.44	0.17	181	4.8	30	46	0.1	70	AS7 - 5637a
M-07-48	X09607	353	355	0.44	0.25	63	7	30	106	5	86	AS7 - 5637a
M-07-48	X09608	355	357	0.39	0.17	62	3.4	25	32	0.1	61	AS7 - 5637a
M-07-48	X09609	357	359	0.52	0.20	74	4.5	30	26	0.1	81	AS7 - 5637a
M-07-48	X09610	359	361	0.49	0.21	82	8.6	35	40	5	87	AS7 - 5637a
M-07-48	X09611	361	363	0.53	0.11	43	3.5	20	10	0.1	106	AS7 - 5637a
M-07-48	X09612	363	365	0.53	0.16	49	4.7	15	18	0.1	91	AS7 - 5637a
M-07-48	X09613	365	367	0.52	0.13	125	2.6	15	18	0.1	82	AS7 - 5637a
M-07-48	X09614	367	369	0.32	0.11	45	1.4	15	14	0.1	93	AS7 - 5637a
M-07-48	X09615	369	371	0.49	0.13	55	3.7	30	20	0.1	75	AS7 - 5637a
M-07-48	X09617	371	373	0.31	0.12	69	3.2	15	10	0.1	80	AS7 - 5637a
M-07-48	X09618	373	375	0.55	0.22	240	2.8	15	30	0.1	93	AS7 - 5637a
M-07-48	X09619	375	377	0.42	0.12	78	2.1	15	14	0.1	77	AS7 - 5637a
M-07-48	X09621	377	379	0.42	0.13	62	4.1	25	28	5	80	AS7 - 5637a
M-07-48	X09622	379	381	0.42	0.13	30	4.7	15	22	0.1	46	AS7-5642a
M-07-48	X09623	381	383	0.51	0.17	63	2	10	18	0.1	49	AS7-5642a
M-07-48	X09624	383	385	0.90	0.32	116	7.9	20	28	5	51	AS7-5642a
M-07-48	X09625	385	387	0.62	0.15	80	5.6	25	16	0.1	44	AS7-5642a
M-07-48	X09626	387	389	0.37	0.12	60	3.5	15	12	0.1	47	AS7-5642a
M-07-48	X09627	389	391	0.43	0.09	27	2.5	15	8	0.1	51	AS7-5642a
M-07-48	X09628	391	393	0.51	0.11	106	4.6	15	10	0.1	56	AS7-5642a
M-07-48	X09629	393	394.39	0.55	0.14	46	5.1	20	20	0.1	52	AS7-5642a
M-07-49	X09630	0	2	0.67	0.16	13	1.7	20	52	0.1	269	AS7-5642a
M-07-49	X09631	2	4	0.60	0.12	13	0.6	15	6	0.1	160	AS7-5642a
M-07-49	X09632	4	6	0.70	0.14	11	1.1	10	12	0.1	100	AS7-5642a
M-07-49	X09633	6	8	0.63	0.12	16	1	20	10	0.1	133	AS7-5642a
M-07-49	X09634	8	10	1.01	0.19	11	1.5	20	34	0.1	91	AS7-5642a
M-07-49	X09635	10	12	0.74	0.17	9	1.2	60	22	5	92	AS7-5642a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-49	X09636	12	14	0.98	0.15	18	1.3	35	20	0.1	86	AS7-5642a
M-07-49	X09637	14	16	1.70	0.22	17	2.1	50	54	0.1	134	AS7-5642a
M-07-49	X09638	16	18	0.86	0.17	12	1.2	20	62	0.1	141	AS7-5642a
M-07-49	X09639	18	20	1.23	0.28	11	2	15	40	0.1	89	AS7-5642a
M-07-49	X09640	20	22	0.74	0.15	21	1.3	20	14	0.1	82	AS7-5642a
M-07-49	X09641	22	24	0.95	0.21	6	1.7	15	40	0.1	73	AS7-5642a
M-07-49	X09642	24	26	1.11	0.19	8	1.3	15	12	0.1	90	AS7-5642a
M-07-49	X09644	26	28	0.79	0.15	8	1	15	14	0.1	102	AS7-5642a
M-07-49	X09645	28	30	0.80	0.14	10	0.9	15	22	0.1	108	AS7-5642a
M-07-49	X09646	30	32	0.68	0.12	8	0.9	15	8	0.1	112	AS7-5642a
M-07-49	X09647	32	34	0.48	0.12	10	1.4	20	24	0.1	134	AS7-5642a
M-07-49	X09649	34	36	0.45	0.08	11	1.2	15	10	0.1	109	AS7-5642a
M-07-49	X09650	36	38	0.65	0.15	11	2.2	25	10	0.1	84	AS7-5642a
M-07-49	X09651	38	40.25	1.05	0.21	7	3	40	18	5	97	AS7-5642a
M-07-49	X09652	40.25	42	0.67	0.30	5	4.8	55	62	20	27	AS7-5642a
M-07-49	X09653	42	44	0.73	0.15	7	2.7	45	30	15	55	AS7-5642a
M-07-49	X09654	44	46	0.95	0.15	5	2.3	45	18	5	71	AS7-5642a
M-07-49	X09655	46	48	2.50	0.14	7	3.3	65	20	10	145	AS7-5642a
M-07-49	X09656	48	50	0.88	0.18	7	3	50	8	15	134	AS7-5642a
M-07-49	X09657	50	52	1.50	0.17	9	4.9	75	38	15	98	AS7-5643a
M-07-49	X09658	52	54	2.70	0.48	17	8.8	160	232	40	521	AS7-5643a
M-07-49	X09659	54	56	1.87	0.30	5	9.8	170	90	60	144	AS7-5643a
M-07-49	X09660	56	58	1.99	0.25	5	8.8	165	82	50	163	AS7-5643a
M-07-49	X09661	58	60	2.40	0.14	7	3.4	145	18	10	192	AS7-5643a
M-07-49	X09662	60	62	1.43	0.20	6	4.2	75	28	5	147	AS7-5643a
M-07-49	X09663	62	64	1.17	0.19	8	3.8	85	24	10	148	AS7-5643a
M-07-49	X09664	64	66	0.91	0.13	10	3.2	100	18	10	131	AS7-5643a
M-07-49	X09666	66	68	1.51	0.22	9	43.2	160	216	90	274	AS7-5643a
M-07-49	X09667	68	69.5	1.10	0.12	7	4.4	100	292	10	540	AS7-5643a
M-07-49	X09668	69.5	71.3	1.07	0.16	7	3	90	24	5	232	AS7-5643a
M-07-49	X09669	71.3	73	0.84	0.22	7	4.9	65	44	10	193	AS7-5643a
M-07-49	X09670	73	75	0.91	0.19	9	6.5	110	54	25	170	AS7-5643a
M-07-49	X09671	75	77	0.49	0.23	7	167	790	488	515	749	AS7-5643a
M-07-49	X09672	77	79	0.50	0.21	6	40.9	205	128	105	174	AS7-5643a
M-07-49	X09673	79	81	1.32	0.27	8	3	45	14	5	138	AS7-5643a
M-07-49	X09674	81	83	0.61	0.67	14	0.01	35	46	5	40	AS7-5643a
M-07-49	X09675	83	85	0.67	0.16	61	1.7	20	26	0.1	216	AS7-5643a
M-07-49	X09676	85	87	1.19	0.24	6	1.9	20	8	0.1	157	AS7-5643a
M-07-49	X09677	87	89	1.17	0.25	6	2.8	30	14	0.1	145	AS7-5643a
M-07-49	X09678	89	91	1.28	0.26	6	4.1	55	40	5	161	AS7-5643a
M-07-49	X09679	91	93	0.71	0.22	6	4.9	25	66	5	62	AS7-5643a
M-07-49	X09680	93	94.5	0.37	0.32	6	7.6	40	172	15	255	AS7-5643a
M-07-49	X09681	94.5	96.15	0.58	0.31	4	5.7	30	62	5	62	AS7-5643a
M-07-49	X09682	96.15	98	0.68	0.18	5	2.6	25	18	0.1	115	AS7-5643a
M-07-49	X09684	98	100	0.84	0.16	6	2.5	25	14	0.1	128	AS7-5643a
M-07-49	X09685	100	102	1.08	0.38	5	15	30	54	5	67	AS7-5643a
M-07-49	X09686	102	104	1.27	0.34	6	6.1	25	20	0.1	91	AS7-5643a
M-07-49	X09687	104	106	0.98	0.19	7	1.6	25	6	0.1	119	AS7-5643a
M-07-49	X09688	106	108	1.24	0.22	7	2.4	30	28	0.1	80	AS7-5643a
M-07-49	X09689	108	110	1.64	0.31	6	2.2	25	10	0.1	100	AS7-5643a
M-07-49	X09690	110	112	0.57	0.30	5	2.5	20	42	0.1	20	AS7-5643a
M-07-49	X09691	112	114	0.64	0.16	8	1.7	25	6	0.1	171	AS7-5643a
M-07-49	X09692	114	116	0.70	0.15	9	2.8	35	16	0.1	171	AS7-5645a
M-07-49	X09693	116	118	0.76	0.21	6	3.3	40	28	0.1	77	AS7-5645a
M-07-49	X09694	118	120	1.23	0.26	7	3.2	20	16	0.1	124	AS7-5645a
M-07-49	X09695	120	122	0.84	0.15	8	2.2	25	8	0.1	133	AS7-5645a
M-07-49	X09696	122	124	1.42	0.27	8	4.1	25	16	0.1	129	AS7-5645a
M-07-49	X09697	124	126	1.13	0.20	9	3.3	50	18	0.1	74	AS7-5645a
M-07-49	X09698	126	128	1.16	0.15	10	2.5	55	18	0.1	86	AS7-5645a
M-07-49	X09700	128	130	0.79	0.31	7	3	20	32	0.1	95	AS7-5645a
M-07-49	X09701	130	132.2	0.94	0.22	9	2.9	20	10	0.1	215	AS7-5645a
M-07-49	X09702	132.2	134.4	0.68	0.20	9	3.8	25	14	0.1	195	AS7-5645a
M-07-49	X09703	134.4	136	0.77	0.28	6	5.5	35	46	0.1	42	AS7-5645a
M-07-49	X09704	136	138	0.85	0.32	7	5.7	20	34	0.1	75	AS7-5645a
M-07-49	X09705	138	140	0.99	0.25	5	5.2	35	28	0.1	30	AS7-5645a
M-07-49	X09706	140	142	0.89	0.25	6	4	40	40	5	75	AS7-5645a
M-07-49	X09707	142	144	0.93	0.25	8	3.4	20	30	0.1	231	AS7-5645a
M-07-49	X09709	144	146	1.08	0.29	6	3.9	25	12	0.1	107	AS7-5645a
M-07-49	X09710	146	148	0.95	0.22	11	2.2	15	8	0.1	71	AS7-5645a
M-07-49	X09711	148	150	0.89	0.23	16	2.4	30	10	0.1	67	AS7-5645a
M-07-49	X09713	150	152	0.82	0.24	9	3.3	50	54	10	25	AS7-5645a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-49	X09714	152	154	0.92	0.29	7	3.8	40	44	10	31	AS7-5645a
M-07-49	X09715	154	156	0.78	0.28	6	4.8	30	68	10	12	AS7-5645a
M-07-49	X09716	156	158	1.08	0.21	6	3.7	100	20	10	75	AS7-5645a
M-07-49	X09717	158	160	3.10	0.14	5	4.2	200	28	10	88	AS7-5645a
M-07-49	X09718	160	162	0.78	0.25	9	4.1	30	42	10	22	AS7-5645a
M-07-49	X09719	162	164	1.09	0.35	6	4	20	26	0.1	50	AS7-5645a
M-07-49	X09720	164	166	0.81	0.31	11	2.8	10	32	0.1	16	AS7-5645a
M-07-49	X09721	166	168	1.40	0.36	5	2.6	15	10	0.1	47	AS7-5645a
M-07-49	X09722	168	170	1.67	0.43	5	2.7	15	8	0.1	37	AS7-5645a
M-07-49	X09723	170	172	1.18	0.23	5	1.8	15	6	0.1	56	AS7-5645a
M-07-49	X09724	172	174	0.80	0.21	5	1.7	25	18	10	34	AS7-5645a
M-07-49	X09725	174	176	1.15	0.26	4	2.1	45	12	5	67	AS7-5645a
M-07-49	X09726	176	178	1.18	0.40	6	3.2	25	18	0.1	45	AS7-5645a
M-07-49	X09727	178	180	1.27	0.29	9	1.7	20	8	0.1	91	AS7-5647a
M-07-49	X09728	180	182	1.23	0.26	7	2	90	16	5	59	AS7-5647a
M-07-49	X09729	182	184	0.69	0.17	11	1.5	30	20	0.1	36	AS7-5647a
M-07-49	X09730	184	186	0.85	0.26	7	2	15	14	0.1	29	AS7-5647a
M-07-49	X09731	186	187.8	0.65	0.18	8	2.2	20	34	5	15	AS7-5647a
M-07-49	X09732	187.8	190	0.87	0.14	9	1	40	10	0.1	68	AS7-5647a
M-07-49	X09733	190	192	0.61	0.19	8	1.2	15	6	0.1	100	AS7-5647a
M-07-49	X09734	192	194	0.82	0.19	4	1.2	25	12	0.1	108	AS7-5647a
M-07-49	X09736	194	196	1.06	0.20	7	1.3	35	14	0.1	55	AS7-5647a
M-07-49	X09737	196	198	0.93	0.22	12	1.5	25	14	0.1	67	AS7-5647a
M-07-49	X09738	198	200	0.84	0.19	5	1.7	30	26	0.1	73	AS7-5647a
M-07-49	X09740	200	202	0.61	0.28	8	3.3	25	62	5	22	AS7-5647a
M-07-49	X09741	202	204	1.44	0.26	7	4.3	35	58	5	143	AS7-5647a
M-07-49	X09742	204	206	0.98	0.22	8	3.7	70	24	5	150	AS7-5647a
M-07-49	X09743	206	208	1.06	0.23	8	3.2	35	22	0.1	118	AS7-5647a
M-07-49	X09744	208	210	1.11	0.24	7	2.6	40	12	0.1	94	AS7-5647a
M-07-49	X09745	210	212	0.63	0.16	6	1.4	25	12	0.1	100	AS7-5647a
M-07-49	X09746	212	214	0.76	0.17	11	1.4	20	14	0.1	88	AS7-5647a
M-07-49	X09747	214	216	0.79	0.28	5	1.9	10	18	0.1	64	AS7-5647a
M-07-49	X09748	216	218	0.61	0.13	5	1.1	15	10	0.1	99	AS7-5647a
M-07-49	X09749	218	220	0.48	0.10	12	1.1	10	16	0.1	112	AS7-5647a
M-07-49	X09750	220	222	1.54	0.22	6	2.8	70	20	0.1	121	AS7-5647a
M-07-49	X09751	222	224	1.04	0.25	4	2.2	25	12	0.1	161	AS7-5647a
M-07-49	X09752	224	226	1.06	0.20	6	1.8	15	16	0.1	118	AS7-5647a
M-07-49	X09753	226	228	0.61	0.15	7	1.4	15	12	0.1	110	AS7-5647a
M-07-49	X09754	228	230	1.08	0.28	5	3	50	22	0.1	126	AS7-5647a
M-07-49	X09755	230	232	1.45	0.37	8	4.4	25	18	0.1	132	AS7-5647a
M-07-49	X09756	232	233.9	1.10	0.16	12	3.3	160	18	0.1	62	AS7-5647a
M-07-49	X09758	233.9	236	1.04	0.16	13	10.5	100	64	5	177	AS7-5647a
M-07-49	X09759	236	238	3.20	0.23	4	114	400	502	65	740	AS7-5647a
M-07-49	X09760	238	240	23.50	0.26	4	237	500	824	160	682	AS7-5647a
M-07-49	X09761	240	242	1.10	0.18	10	68.8	480	182	130	369	AS7-5647a
M-07-49	X09762	242	244	2.68	0.20	14	59.8	320	230	145	546	AS7-5653a
M-07-49	X09763	244	246	1.01	0.16	23	18.2	130	94	60	109	AS7-5653a
M-07-49	X09764	246	248	0.70	0.20	16	14.1	120	60	65	227	AS7-5653a
M-07-49	X09765	248	250	1.13	0.16	18	12.1	100	36	60	104	AS7-5653a
M-07-49	X09766	250	251.65	1.52	0.16	15	6.2	50	50	5	92	AS7-5653a
M-07-49	X09767	251.65	253	0.91	0.25	13	4.7	0.1	26	5	89	AS7-5653a
M-07-49	X09768	253	255	1.49	0.35	16	4.2	0.1	44	30	149	AS7-5653a
M-07-49	X09769	255	257	0.78	0.26	13	2.1	0.1	28	10	84	AS7-5653a
M-07-49	X09770	257	259	0.70	0.23	16	1.9	0.1	34	25	94	AS7-5653a
M-07-49	X09771	259	261	1.70	0.22	12	2.8	10	32	0.1	40	AS7-5653a
M-07-49	X09772	261	263	0.92	0.18	25	1.5	15	28	30	118	AS7-5653a
M-07-49	X09774	263	265	0.89	0.32	14	2.3	0.1	30	10	113	AS7-5653a
M-07-49	X09775	265	267	0.66	0.24	20	1.2	0.1	40	40	108	AS7-5653a
M-07-49	X09777	267	269	0.55	0.26	17	1.4	0.1	36	15	68	AS7-5653a
M-07-49	X09778	269	271	1.15	0.33	18	2	0.1	30	20	78	AS7-5653a
M-07-49	X09779	271	273	1.15	0.28	19	2.5	0.1	40	15	123	AS7-5653a
M-07-49	X09780	273	275	0.83	0.15	19	1.4	0.1	42	15	80	AS7-5653a
M-07-49	X09781	275	277	0.94	0.21	19	1.7	0.1	40	0.1	57	AS7-5653a
M-07-49	X09782	277	279	0.83	0.12	19	0.6	0.1	24	15	102	AS7-5653a
M-07-49	X09783	279	280.25	1.77	0.29	17	2.5	5	28	15	158	AS7-5653a
M-07-49	X09784	280.25	281.5	0.44	0.14	20	0.9	0.1	24	20	171	AS7-5653a
M-07-49	X09785	281.5	283	1.23	0.35	21	3.3	0.1	78	5	95	AS7-5653a
M-07-49	X09786	283	285	1.65	0.21	13	13.8	120	66	85	185	AS7-5653a
M-07-49	X09787	285	287	1.35	0.14	17	5.7	50	66	10	155	AS7-5653a
M-07-49	X09788	287	289	0.79	0.15	17	3.4	25	22	0.1	132	AS7-5653a
M-07-49	X09789	289	291	1.46	0.25	13	3.5	30	68	0.1	85	AS7-5653a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-49	X09790	291	293	1.71	0.17	13	3.3	20	54	0.1	95	AS7-5653a
M-07-49	X09791	293	295	1.03	0.19	16	2.8	10	38	10	129	AS7-5653a
M-07-49	X09792	295	297	0.78	0.21	18	2.8	0.1	34	10	72	AS7-5653a
M-07-49	X09793	297	298.1	2.03	0.16	17	3.3	15	82	0.1	116	AS7-5653a
M-07-49	X09794	298.1	300	0.85	0.27	25	2.5	0.1	52	25	170	AS7-5653a
M-07-49	X09795	300	302	0.67	0.19	19	1.7	10	56	20	169	AS7-5653a
M-07-49	X09796	302	304	0.62	0.17	19	1	0.1	34	20	170	AS7-5653a
M-07-49	X09797	304	306	1.13	0.32	11	2.8	0.1	56	10	119	AS7-5656a
M-07-49	X09798	306	308	0.93	0.23	10	1.8	0.1	24	15	128	AS7-5656a
M-07-49	X09799	308	310	1.11	0.19	16	2.5	0.1	136	15	169	AS7-5656a
M-07-49	X09800	310	312	2.14	0.22	16	3.1	5	52	25	177	AS7-5656a
M-07-49	X09801	312	314	0.63	0.24	24	2.1	0.1	32	15	113	AS7-5656a
M-07-49	X09802	314	316	2.70	0.36	22	3.4	5	70	5	93	AS7-5656a
M-07-49	X09803	316	318	1.17	0.23	14	1.9	15	30	10	150	AS7-5656a
M-07-49	X09804	318	320	2.19	0.17	13	1.7	0.1	38	20	136	AS7-5656a
M-07-49	X09805	320	322	0.81	0.18	18	2.1	0.1	54	15	170	AS7-5656a
M-07-49	X09806	322	324	0.44	0.11	23	2	0.1	106	10	81	AS7-5656a
M-07-49	X09807	324	326	0.48	0.16	15	1.7	0.1	32	15	38	AS7-5656a
M-07-49	X09809	326	328	0.38	0.11	20	1.1	0.1	32	10	69	AS7-5656a
M-07-49	X09810	328	330	0.83	0.23	12	1.8	0.1	42	10	93	AS7-5656a
M-07-49	X09811	330	332	0.65	0.15	17	1.3	0.1	48	15	204	AS7-5656a
M-07-49	X09813	332	334	0.77	0.26	13	2	0.1	54	15	78	AS7-5656a
M-07-49	X09814	334	336	0.96	0.32	12	2.4	0.1	32	20	96	AS7-5656a
M-07-49	X09815	336	338	0.63	0.17	20	1.9	0.1	44	20	145	AS7-5656a
M-07-49	X09816	338	340	0.47	0.15	16	2	0.1	30	10	141	AS7-5656a
M-07-49	X09817	340	341.38	0.91	0.21	21	2.8	0.1	24	25	168	AS7-5656a
M-07-49	X09818	341.38	343	0.59	0.16	21	3.4	15	86	20	41	AS7-5656a
M-07-49	X09819	343	345	0.73	0.21	12	1.8	0.1	58	0.1	188	AS7-5656a
M-07-49	X09820	345	347	0.73	0.66	14	6.3	0.1	110	10	149	AS7-5656a
M-07-49	X09821	347	349	0.94	0.33	13	2.7	0.1	30	10	144	AS7-5656a
M-07-49	X09822	349	351	0.88	0.30	9	2.3	0.1	30	10	52	AS7-5656a
M-07-49	X09823	351	353	0.94	0.27	10	2.1	0.1	36	0.1	73	AS7-5656a
M-07-49	X09824	353	355	0.98	0.28	14	2.7	0.1	40	10	54	AS7-5656a
M-07-49	X09825	355	357	0.36	0.28	12	2.9	55	40	25	40	AS7-5656a
M-07-49	X09826	357	359	0.37	0.19	107	1.8	0.1	30	10	50	AS7-5656a
M-07-49	X09827	359	361	0.50	0.22	10	1.8	0.1	36	0.1	32	AS7-5656a
M-07-49	X09828	361	363	0.55	0.21	36	2	0.1	38	0.1	169	AS7-5656a
M-07-49	X09829	363	365	0.52	0.26	11	2.3	0.1	84	15	209	AS7-5656a
M-07-49	X09830	365	367	0.78	0.22	9	2.4	0.1	50	5	106	AS7-5656a
M-07-49	X09831	367	369.1	1.01	0.22	10	1.9	0.1	22	5	66	AS7-5656a
M-07-49	X09832	369.1	371	0.59	0.14	15	2.7	10	68	0.1	204	AS7-5657a
M-07-49	X09833	371	373	0.72	0.12	21	1.4	15	26	0.1	101	AS7-5657a
M-07-49	X09834	373	375	0.95	0.14	17	1.8	20	14	0.1	123	AS7-5657a
M-07-49	X09835	375	377	0.62	0.19	13	2.2	15	52	0.1	49	AS7-5657a
M-07-49	X09836	377	379	1.43	0.25	12	2.2	15	38	0.1	135	AS7-5657a
M-07-49	X09837	379	381	1.01	0.20	9	1.9	25	14	0.1	267	AS7-5657a
M-07-49	X09838	381	383	0.70	0.13	12	1.4	20	12	0.1	190	AS7-5657a
M-07-49	X09839	383	385	0.66	0.10	13	1.4	10	26	0.1	104	AS7-5657a
M-07-49	X09840	385	387	0.51	0.10	18	1.3	10	18	0.1	151	AS7-5657a
M-07-49	X09841	387	389	0.60	0.11	19	1.3	10	20	0.1	146	AS7-5657a
M-07-49	X09842	389	391	0.72	0.18	15	1.5	10	18	0.1	97	AS7-5657a
M-07-49	X09843	391	393	0.65	0.16	13	1.5	5	12	0.1	78	AS7-5657a
M-07-49	X09844	393	395	0.65	0.16	16	1.5	10	18	0.1	72	AS7-5657a
M-07-49	X09845	395	396.85	0.54	0.14	112	1.3	10	16	0.1	73	AS7-5657a
M-07-50	X05191	3.05	5	0.91	0.11	54	2.2	20	52	0.1	264	AS7-5646a
M-07-50	X05192	5	7	0.75	0.26	73	3.5	40	116	15	173	AS7-5646a
M-07-50	X05193	7	9	1.12	0.17	72	2.1	15	72	0.1	160	AS7-5646a
M-07-50	X05194	9	11	0.80	0.15	53	1.9	5	60	0.1	212	AS7-5646a
M-07-50	X05195	11	13	0.90	0.17	42	1.7	10	48	0.1	255	AS7-5646a
M-07-50	X05196	13	15	0.95	0.18	53	1.8	10	74	0.1	431	AS7-5646a
M-07-50	X05197	15	17	0.86	0.19	71	2.3	10	64	0.1	171	AS7-5646a
M-07-50	X05198	17	19	0.57	0.19	86	2.5	5	154	0.1	1222	AS7-5646a
M-07-50	X05199	19	21	0.79	0.20	123	2.1	35	122	10	555	AS7-5646a
M-07-50	X05201	21	23	0.85	0.18	123	2.3	10	110	0.1	763	AS7-5646a
M-07-50	X05202	23	25	0.86	0.18	58	2.1	10	80	0.1	345	AS7-5646a
M-07-50	X05203	25	27	0.62	0.16	52	2.3	10	66	0.1	242	AS7-5651a
M-07-50	X05204	27	29	0.83	0.14	44	2.8	15	46	0.1	315	AS7-5651a
M-07-50	X05205	29	31	0.76	0.16	36	3.4	15	170	0.1	447	AS7-5651a
M-07-50	X05206	31	33	0.80	0.17	57	2.3	10	70	0.1	152	AS7-5651a
M-07-50	X05207	33	35	0.63	0.18	42	2.1	10	46	0.1	124	AS7-5651a
M-07-50	X05208	35	37	1.12	0.16	117	2.6	10	78	0.1	766	AS7-5651a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-50	X05209	37	39	0.57	0.17	60	1.9	5	44	0.1	138	AS7-5651a
M-07-50	X05210	39	41	0.96	0.19	69	1.8	10	40	0.1	172	AS7-5651a
M-07-50	X05211	41	43	0.68	0.20	87	1.5	10	84	0.1	253	AS7-5651a
M-07-50	X05212	43	45	0.51	0.20	76	1.4	10	88	0.1	387	AS7-5651a
M-07-50	X05213	45	47	0.56	0.23	57	2.1	65	104	40	102	AS7-5651a
M-07-50	X05214	47	49	0.49	0.13	77	2	65	96	45	190	AS7-5651a
M-07-50	X05215	49	51	0.51	0.16	58	2.1	20	158	0.1	687	AS7-5651a
M-07-50	X05216	51	53	1.27	0.19	73	1	10	30	0.1	56	AS7-5651a
M-07-50	X05217	53	55	1.35	0.16	70	0.6	10	20	0.1	85	AS7-5651a
M-07-50	X05218	55	57	1.26	0.17	83	1.3	20	28	0.1	147	AS7-5651a
M-07-50	X05219	57	59	1.29	0.17	49	1	15	26	0.1	98	AS7-5651a
M-07-50	X05220	59	61	1.06	0.17	42	1.1	10	30	0.1	224	AS7-5651a
M-07-50	X05221	61	63	0.84	0.18	59	1.1	10	42	0.1	70	AS7-5651a
M-07-50	X05222	63	65	0.68	0.17	62	1.1	10	74	0.1	428	AS7-5651a
M-07-50	X05223	65	67	1.10	0.17	82	1.1	10	40	0.1	102	AS7-5651a
M-07-50	X05224	67	69	0.84	0.21	70	1.2	15	32	0.1	21	AS7-5651a
M-07-50	X05225	69	71	1.42	0.20	84	2.1	170	94	80	98	AS7-5651a
M-07-50	X05227	71	73	1.27	0.21	101	2.2	90	48	55	78	AS7-5651a
M-07-50	X05228	73	75	1.51	0.18	125	1.3	20	32	5	45	AS7-5651a
M-07-50	X05229	75	77	0.88	0.17	162	1.2	15	26	0.1	36	AS7-5651a
M-07-50	X05230	77	79	1.41	0.19	55	1.2	10	22	0.1	48	AS7-5651a
M-07-50	X05231	79	81	0.64	0.15	53	1	20	44	0.1	72	AS7-5651a
M-07-50	X05232	81	83	0.91	0.15	54	1.1	15	32	0.1	83	AS7-5651a
M-07-50	X05233	83	85	1.11	0.17	58	1	35	42	0.1	81	AS7-5651a
M-07-50	X05236	85	87	1.43	0.14	69	0.9	25	32	0.1	36	AS7-5651a
M-07-50	X05237	87	89	0.88	0.13	51	0.9	10	30	0.1	45	AS7-5651a
M-07-50	X05238	89	91	0.83	0.13	87	0.8	0.1	48	0.1	149	AS7-5652a
M-07-50	X05239	91	93	0.95	0.15	100	0.8	0.1	30	0.1	77	AS7-5652a
M-07-50	X05240	93	95	1.14	0.17	91	0.9	0.1	28	0.1	47	AS7-5652a
M-07-50	X05241	95	97	0.71	0.15	176	1.3	5	102	10	60	AS7-5652a
M-07-50	X05242	97	99	0.35	0.10	59	0.7	0.1	74	0.1	48	AS7-5652a
M-07-50	X05243	99	101	1.26	0.13	78	1	20	32	10	37	AS7-5652a
M-07-50	X05244	101	103	1.21	0.13	55	1.3	0.1	30	0.1	49	AS7-5652a
M-07-50	X05245	103	105	0.97	0.11	53	0.8	0.1	30	0.1	60	AS7-5652a
M-07-50	X05246	105	107	0.92	0.18	53	2.4	0.1	38	0.1	91	AS7-5652a
M-07-50	X05247	107	109	1.06	0.17	68	2	0.1	36	0.1	72	AS7-5652a
M-07-50	X05248	109	111	4.20	0.15	61	2.6	0.1	42	0.1	115	AS7-5652a
M-07-50	X05249	111	113	0.66	0.16	38	2.3	0.1	48	5	114	AS7-5652a
M-07-50	X05251	113	115	0.85	0.16	44	2.1	5	58	0.1	115	AS7-5652a
M-07-50	X05252	115	117	0.98	0.16	52	1.9	0.1	52	0.1	276	AS7-5652a
M-07-50	X05253	117	119	0.65	0.22	119	1.7	0.1	40	0.1	145	AS7-5652a
M-07-50	X05254	119	121	0.91	0.19	83	1.9	0.1	46	0.1	93	AS7-5652a
M-07-50	X05255	121	123.45	0.69	0.19	77	1.4	0.1	32	0.1	89	AS7-5652a
M-07-50	X05256	123.45	126.15	0.27	0.01	7	0.3	40	34	0.1	129	AS7-5652a
M-07-50	X05257	126.15	128	0.68	0.12	37	0.9	0.1	26	0.1	79	AS7-5652a
M-07-50	X05258	128	130	0.81	0.18	66	1.5	0.1	60	0.1	82	AS7-5652a
M-07-50	X05259	130	132	1.02	0.29	82	1.7	0.1	32	5	54	AS7-5652a
M-07-50	X05261	132	134	0.93	0.18	46	1.5	0.1	32	0.1	39	AS7-5652a
M-07-50	X05262	134	136	0.62	0.16	54	2.2	20	54	0.1	146	AS7-5652a
M-07-50	X05263	136	138	0.74	0.15	85	1.8	0.1	62	0.1	229	AS7-5652a
M-07-50	X05264	138	140	1.38	0.17	154	2	0.1	34	0.1	149	AS7-5652a
M-07-50	X05265	140	142	0.46	0.14	83	1.4	0.1	36	0.1	91	AS7-5652a
M-07-50	X05266	142	144	0.62	0.17	175	1.8	0.1	54	0.1	104	AS7-5652a
M-07-50	X05267	144	146	0.55	0.13	101	1.5	0.1	38	0.1	141	AS7-5652a
M-07-50	X05268	146	148	0.43	0.21	113	1.6	0.1	46	0.1	267	AS7-5652a
M-07-50	X05269	148	149.3	0.41	0.11	80	1.3	0.1	80	0.1	110	AS7-5652a
M-07-50	X05270	149.3	151.25	0.07	0.01	17	0.2	45	132	35	176	AS7-5652a
M-07-50	X05271	151.25	153	0.74	0.15	93	1.6	0.1	128	5	305	AS7-5652a
M-07-50	X05272	153	155	0.55	0.13	61	1.3	0.1	64	5	222	AS7-5652a
M-07-50	X05273	155	157	0.59	0.12	73	1.6	0.1	94	10	111	AS7-5654a
M-07-50	X05274	157	159	0.72	0.14	96	1.7	0.1	80	5	122	AS7-5654a
M-07-50	X05275	159	161	0.68	0.15	90	1.8	0.1	62	5	150	AS7-5654a
M-07-50	X05276	161	163	0.53	0.12	90	1.3	0.1	46	0.1	110	AS7-5654a
M-07-50	X05277	163	165	0.81	0.16	79	1.6	0.1	52	0.1	104	AS7-5654a
M-07-50	X05278	165	167	0.80	0.15	97	2.1	0.1	58	0.1	88	AS7-5654a
M-07-50	X05279	167	169	1.09	0.16	56	1.9	0.1	58	0.1	92	AS7-5654a
M-07-50	X05280	169	171	0.72	0.17	62	3.6	0.1	92	10	121	AS7-5654a
M-07-50	X05281	171	173	0.63	0.14	77	2.1	0.1	46	5	98	AS7-5654a
M-07-50	X05282	173	175	0.85	0.17	145	2.8	0.1	54	0.1	90	AS7-5654a
M-07-50	X05283	175	177	0.45	0.13	100	2.3	0.1	84	0.1	74	AS7-5654a
M-07-50	X05284	177	179	0.66	0.14	194	1.8	0.1	74	0.1	112	AS7-5654a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-50	X05285	179	181	0.81	0.14	99	1.6	0.1	68	0.1	169	AS7-5654a
M-07-50	X05286	181	183	1.12	0.17	124	1.9	0.1	66	0.1	155	AS7-5654a
M-07-50	X05287	183	185	0.70	0.12	125	1.1	0.1	82	10	156	AS7-5654a
M-07-50	X05288	185	187	0.60	0.13	89	1.4	0.1	78	0.1	131	AS7-5654a
M-07-50	X05289	187	189	0.78	0.14	79	1.5	0.1	92	0.1	188	AS7-5654a
M-07-50	X05290	189	191	0.70	0.12	130	1.2	0.1	70	10	120	AS7-5654a
M-07-50	X05292	191	193	0.61	0.11	81	1.1	0.1	68	5	100	AS7-5654a
M-07-50	X05293	193	195	0.47	0.10	87	1	0.1	68	15	124	AS7-5654a
M-07-50	X05294	195	197	0.46	0.06	104	0.8	0.1	78	10	103	AS7-5654a
M-07-50	X05295	197	199	0.72	0.15	109	1.4	0.1	90	10	141	AS7-5654a
M-07-50	X05296	199	201	0.64	0.13	85	1.8	0.1	88	0.1	124	AS7-5654a
M-07-50	X05297	201	203	0.49	0.10	205	1.3	0.1	64	10	97	AS7-5654a
M-07-50	X05300	203	205	0.81	0.11	118	1.6	0.1	96	15	97	AS7-5654a
M-07-50	X05301	205	207	0.73	0.13	63	1.2	0.1	60	20	94	AS7-5654a
M-07-50	X05302	207	209	0.58	0.12	178	1	0.1	56	10	115	AS7-5654a
M-07-50	X05303	209	211	0.54	0.11	100	1.3	0.1	46	10	70	AS7-5654a
M-07-50	X05304	211	213	0.69	0.12	82	1.2	0.1	46	10	68	AS7-5654a
M-07-50	X05305	213	215	0.37	0.11	86	1.2	30	58	10	50	AS7-5654a
M-07-50	X05306	215	217	0.26	0.12	58	1.3	75	70	20	45	AS7-5654a
M-07-50	X05307	217	219	0.48	0.14	106	1.4	60	74	10	40	AS7-5654a
M-07-50	X05308	219	221	0.49	0.09	67	0.8	0.1	38	0.1	42	AS7-5655a
M-07-50	X05309	221	223	0.46	0.12	117	1.3	0.1	52	0.1	57	AS7-5655a
M-07-50	X05310	223	225	0.45	0.09	83	1.1	5	34	15	110	AS7-5655a
M-07-50	X05311	225	227	0.51	0.12	141	1.3	0.1	32	10	84	AS7-5655a
M-07-50	X05312	227	229	0.46	0.10	100	1.6	5	38	0.1	82	AS7-5655a
M-07-50	X05313	229	231	0.37	0.10	61	1.1	10	34	0.1	83	AS7-5655a
M-07-50	X05314	231	233	0.51	0.13	241	1.4	10	32	0.1	88	AS7-5655a
M-07-50	X05315	233	235	0.46	0.09	65	1.8	105	30	0.1	89	AS7-5655a
M-07-50	X05316	235	237	0.37	0.11	73	2.1	0.1	50	20	86	AS7-5655a
M-07-50	X05317	237	239	0.28	0.07	260	1.4	0.1	70	15	125	AS7-5655a
M-07-50	X05318	239	241	0.41	0.10	117	1.9	0.1	76	20	149	AS7-5655a
M-07-50	X05319	241	243.1	0.57	0.11	96	1.6	0.1	124	0.1	235	AS7-5655a
M-07-50	X05320	243.1	244.8	0.13	0.03	27	1.5	80	618	0.1	154	AS7-5655a
M-07-50	X05321	244.8	247.3	0.18	0.06	49	2.1	135	184	50	344	AS7-5655a
M-07-50	X05322	247.3	249.9	0.44	0.06	84	2.8	165	420	85	452	AS7-5655a
M-07-50	X05323	249.9	252	0.17	0.05	58	1.1	40	124	35	257	AS7-5655a
M-07-50	X05324	252	254	0.16	0.02	60	0.3	10	52	25	145	AS7-5655a
M-07-50	X05325	254	256	0.18	0.03	173	0.5	10	72	25	88	AS7-5655a
M-07-50	X05326	256	258	0.16	0.03	98	0.4	10	68	10	105	AS7-5655a
M-07-50	X05327	258	260	0.39	0.08	64	0.7	0.1	122	40	106	AS7-5655a
M-07-50	X05328	260	262	0.30	0.06	29	0.6	0.1	60	25	98	AS7-5655a
M-07-50	X05329	262	264	0.18	0.03	50	0.2	0.1	58	40	90	AS7-5655a
M-07-50	X05330	264	266	0.37	0.03	60	0.5	0.1	36	30	85	AS7-5655a
M-07-50	X05331	266	268	0.24	0.03	26	0.4	0.1	26	15	61	AS7-5655a
M-07-50	X05332	268	270	0.14	0.03	64	0.3	0.1	28	30	63	AS7-5655a
M-07-50	X05333	270	272	0.31	0.03	68	0.4	0.1	22	10	53	AS7-5655a
M-07-50	X05334	272	273.4	0.32	0.03	20	0.3	0.1	22	10	62	AS7-5655a
M-07-50	X05336	273.4	276	0.39	0.04	26	0.4	0.1	28	10	30	AS7-5655a
M-07-50	X05337	276	278	0.30	0.03	43	0.5	0.1	28	5	34	AS7-5655a
M-07-50	X05338	278	280	0.23	0.04	18	0.4	0.1	24	10	44	AS7-5655a
M-07-50	X05339	280	282	0.30	0.05	25	0.5	0.1	24	25	36	AS7-5655a
M-07-50	X05341	282	284	0.89	0.10	43	1.8	0.1	26	0.1	73	AS7-5655a
M-07-50	X05342	284	285.6	1.53	0.07	46	2.8	15	52	80	189	AS7-5655a
M-07-50	X05343	285.6	288	0.49	0.04	60	1.2	0.1	44	0.1	40	AS7-5667a
M-07-50	X05344	288	290	0.56	0.04	47	0.5	0.1	40	0.1	54	AS7-5667a
M-07-50	X05346	290	292	0.38	0.04	25	0.3	0.1	36	0.1	34	AS7-5667a
M-07-50	X05347	292	294	0.21	0.04	28	0.5	0.1	26	0.1	25	AS7-5667a
M-07-50	X05348	294	296	0.38	0.05	31	0.3	10	34	0.1	54	AS7-5667a
M-07-50	X05349	296	298	0.22	0.04	72	0.4	0.1	34	0.1	37	AS7-5667a
M-07-50	X05351	298	300	0.14	0.02	31	0.3	0.1	34	0.1	21	AS7-5667a
M-07-50	X05352	300	302	0.15	0.03	61	0.4	0.1	34	0.1	21	AS7-5667a
M-07-50	X05353	302	304	0.06	0.01	154	0.3	0.1	24	0.1	7	AS7-5667a
M-07-50	X05354	304	306	0.04	0.01	96	0.2	0.1	24	0.1	7	AS7-5667a
M-07-50	X05355	306	308	0.05	0.02	93	0.2	0.1	20	0.1	8	AS7-5667a
M-07-50	X05356	308	310	0.07	0.02	126	0.2	0.1	22	0.1	19	AS7-5667a
M-07-50	X05357	310	312	0.08	0.03	25	0.3	0.1	28	0.1	14	AS7-5667a
M-07-50	X05358	312	314	0.10	0.04	71	1	35	46	5	67	AS7-5667a
M-07-50	X05359	314	316	0.22	0.03	46	0.4	0.1	42	0.1	36	AS7-5667a
M-07-50	X05361	316	318	0.52	0.02	46	0.6	10	32	0.1	40	AS7-5667a
M-07-50	X05362	318	320	0.14	0.02	21	0.5	15	82	0.1	47	AS7-5667a
M-07-50	X05363	320	322	0.09	0.03	51	0.4	10	66	0.1	32	AS7-5667a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-50	X05364	322	324	0.24	0.03	211	0.5	10	86	5	129	AS7-5667a
M-07-50	X05365	324	326	0.27	0.03	113	0.2	0.1	44	0.1	182	AS7-5667a
M-07-50	X05366	326	328	0.23	0.03	49	0.2	0.1	28	0.1	31	AS7-5667a
M-07-50	X05367	328	330	0.24	0.04	65	0.3	0.1	30	0.1	35	AS7-5667a
M-07-50	X05368	330	332	0.21	0.05	101	0.9	30	42	10	47	AS7-5667a
M-07-50	X05369	332	334	0.06	0.02	27	0.5	10	44	0.1	21	AS7-5667a
M-07-50	X05370	334	336	0.41	0.04	129	0.6	0.1	34	0.1	53	AS7-5667a
M-07-50	X05371	336	338	0.20	0.03	96	0.7	10	62	10	39	AS7-5667a
M-07-50	X05372	338	340	0.31	0.06	56	0.8	15	64	5	46	AS7-5667a
M-07-50	X05373	340	342.9	0.23	0.05	127	0.6	5	44	0.1	38	AS7-5667a
M-07-51	X09846	9.14	11	1.30	0.23	13	3	25	24	0.1	36	AS7-5657a
M-07-51	X09847	11	13	1.22	0.27	8	3.9	35	22	0.1	38	AS7-5657a
M-07-51	X09848	13	15	1.16	0.28	11	4	50	64	0.1	65	AS7-5657a
M-07-51	X09849	15	17	1.13	0.31	10	3.6	20	26	0.1	59	AS7-5657a
M-07-51	X09850	17	19	1.29	0.32	10	3.2	45	16	0.1	57	AS7-5657a
M-07-51	X09852	19	21	2.70	0.23	9	3.7	90	28	0.1	77	AS7-5657a
M-07-51	X09853	21	23	3.40	0.16	12	4.5	115	50	15	61	AS7-5657a
M-07-51	X09854	23	25	1.32	0.34	15	4.5	60	24	0.1	145	AS7-5657a
M-07-51	X09855	25	26.25	0.96	0.37	18	4.4	10	18	0.1	17	AS7-5657a
M-07-51	X09856	26.25	27.5	1.10	0.15	24	2.3	15	16	0.1	11	AS7-5657a
M-07-51	X09857	28.5	30	1.15	0.29	13	4.2	30	34	10	16	AS7-5657a
M-07-51	X09858	30	32	1.26	0.36	10	5.5	90	36	55	39	AS7-5657a
M-07-51	X09859	32	33.3	2.90	0.34	8	4.4	40	20	10	30	AS7-5657a
M-07-51	X09860	33.3	35	1.46	0.36	10	4	35	16	0.1	38	AS7-5657a
M-07-51	X09861	35	37	1.45	0.40	11	3.9	30	24	0.1	55	AS7-5657a
M-07-51	X09863	37	39	1.47	0.35	53	6.4	50	258	0.1	37	AS7-5657a
M-07-51	X09864	39	41	1.17	0.35	16	3.8	40	16	0.1	60	AS7-5657a
M-07-51	X09865	41	43	0.88	0.25	11	2.8	20	28	0.1	51	AS7-5657a
M-07-51	X09866	43	45	1.52	0.63	8	5.8	25	34	0.1	54	AS7-5657a
M-07-51	X09867	45	47	1.05	0.26	18	3	25	28	5	35	AS7-5658a
M-07-51	X09868	47	49	1.10	0.31	14	3.6	30	34	0.1	34	AS7-5658a
M-07-51	X09869	49	51	1.12	0.33	15	4.2	10	38	0.1	27	AS7-5658a
M-07-51	X09870	51	53	0.92	0.28	18	3	20	40	10	34	AS7-5658a
M-07-51	X09871	53	55	0.86	0.25	19	2.7	10	28	0.1	47	AS7-5658a
M-07-51	X09872	55	57	0.87	0.27	14	2.8	0.1	32	5	56	AS7-5658a
M-07-51	X09873	57	59	1.27	0.32	13	4	35	32	0.1	35	AS7-5658a
M-07-51	X09874	59	61	1.15	0.30	18	3.6	35	30	0.1	41	AS7-5658a
M-07-51	X09875	61	63	1.29	0.45	10	4.1	15	24	0.1	25	AS7-5658a
M-07-51	X09876	63	65	0.74	0.37	11	3.7	0.1	36	0.1	49	AS7-5658a
M-07-51	X09877	65	67	1.23	0.54	12	4.7	0.1	34	0.1	44	AS7-5658a
M-07-51	X09878	67	69	0.74	0.26	12	3.1	0.1	30	0.1	46	AS7-5658a
M-07-51	X09879	69	71	0.78	0.34	22	3.7	0.1	28	10	46	AS7-5658a
M-07-51	X09880	71	73	0.69	0.26	19	3.2	0.1	36	0.1	18	AS7-5658a
M-07-51	X09881	73	75	0.79	0.22	19	2.6	20	26	10	48	AS7-5658a
M-07-51	X09882	75	77	0.74	0.22	16	2.6	0.1	32	5	63	AS7-5658a
M-07-51	X09884	77	79	0.72	0.24	12	3.1	0.1	30	0.1	28	AS7-5658a
M-07-51	X09885	79	81	0.34	0.23	10	2.5	0.1	22	0.1	19	AS7-5658a
M-07-51	X09886	81	83	0.51	0.27	15	3.1	0.1	28	10	50	AS7-5658a
M-07-51	X09887	83	85	0.62	0.26	21	4.1	0.1	42	0.1	59	AS7-5658a
M-07-51	X09889	85	87	0.73	0.22	22	4.7	15	38	0.1	63	AS7-5658a
M-07-51	X09890	87	89	1.02	0.50	67	6	0.1	76	0.1	34	AS7-5658a
M-07-51	X09891	89	91	1.11	0.34	20	3.6	0.1	36	30	60	AS7-5658a
M-07-51	X09892	91	93	0.94	0.34	12	3.7	0.1	34	0.1	57	AS7-5658a
M-07-51	X09893	93	95	1.07	0.42	12	5.1	0.1	34	5	29	AS7-5658a
M-07-51	X09895	95	97	0.76	0.32	25	3.9	0.1	44	10	58	AS7-5658a
M-07-51	X09896	97	99	0.61	0.21	26	3.2	0.1	40	5	60	AS7-5658a
M-07-51	X09897	99	101	0.69	0.23	13	3	0.1	34	10	54	AS7-5658a
M-07-51	X09898	101	103	0.71	0.22	11	2.9	0.1	98	0.1	82	AS7-5658a
M-07-51	X09899	103	105	0.52	0.14	16	1.6	0.1	38	10	85	AS7-5658a
M-07-51	X09900	105	107	0.43	0.19	106	2.6	0.1	32	10	52	AS7-5658a
M-07-51	X09901	107	109	1.11	0.34	12	3.6	0.1	34	10	55	AS7-5658a
M-07-51	X09902	109	111	1.02	0.32	11	3.9	0.1	32	10	43	AS7-5659a
M-07-51	X09903	111	113	1.13	0.37	13	4.3	0.1	40	10	43	AS7-5659a
M-07-51	X09904	113	114.45	1.02	0.40	19	4.8	0.1	22	10	52	AS7-5659a
M-07-51	X09905	114.45	116	0.75	0.78	25	6.9	15	48	0.1	48	AS7-5659a
M-07-51	X09906	116	118	0.68	0.38	14	4.4	0.1	36	0.1	39	AS7-5659a
M-07-51	X09907	118	120	0.80	0.23	13	5.6	65	40	0.1	63	AS7-5659a
M-07-51	X09908	120	122	0.67	0.23	18	50	80	116	80	276	AS7-5659a
M-07-51	X09909	122	124	0.47	0.19	53	34	185	52	275	154	AS7-5659a
M-07-51	X09910	124	126	0.52	0.24	15	82	425	100	455	181	AS7-5659a
M-07-51	X09911	126	128	0.66	0.21	14	66	285	60	200	141	AS7-5659a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-51	X09912	128	130	0.73	0.22	23	5.1	10	28	20	38	AS7-5659a
M-07-51	X09913	130	132	0.73	0.19	11	2.4	0.1	32	10	41	AS7-5659a
M-07-51	X09915	132	134	1.14	0.32	15	3.4	0.1	34	10	52	AS7-5659a
M-07-51	X09916	134	136	0.86	0.17	15	3	10	42	10	63	AS7-5659a
M-07-51	X09917	136	138	0.91	0.11	17	5.6	85	46	5	190	AS7-5659a
M-07-51	X09919	138	140	0.69	0.10	15	3.2	75	36	10	43	AS7-5659a
M-07-51	X09920	140	142	1.05	0.26	31	7.6	45	30	5	36	AS7-5659a
M-07-51	X09921	142	143.6	0.70	0.28	14	6.9	70	48	20	53	AS7-5659a
M-07-51	X09922	143.6	145	0.89	0.25	21	3.7	0.1	32	15	93	AS7-5659a
M-07-51	X09923	145	146.25	0.82	0.30	44	5	5	34	20	67	AS7-5659a
M-07-51	X09924	147.4	149	0.90	0.31	93	4.1	0.1	44	10	63	AS7-5659a
M-07-51	X09925	149	151	0.85	0.24	54	2.8	0.1	48	10	47	AS7-5659a
M-07-51	X09926	151	153	0.91	0.28	55	2.7	0.1	32	5	54	AS7-5659a
M-07-51	X09927	153	155	0.63	0.21	18	2	0.1	38	10	47	AS7-5659a
M-07-51	X09928	155	157	0.42	0.15	17	1.6	0.1	28	5	51	AS7-5659a
M-07-51	X09929	157	159	0.51	0.15	30	1.8	0.1	32	5	68	AS7-5659a
M-07-51	X09930	159	161	0.57	0.24	29	2.5	0.1	26	0.1	51	AS7-5659a
M-07-51	X09931	161	163	0.28	0.19	22	2	0.1	30	10	52	AS7-5659a
M-07-51	X09932	163	165	0.89	0.38	27	3.7	10	36	10	45	AS7-5659a
M-07-51	X09933	165	167	0.59	0.36	20	3.7	0.1	36	15	47	AS7-5659a
M-07-51	X09934	167	169	1.09	0.33	27	4.6	10	34	15	54	AS7-5659a
M-07-51	X09935	169	171	0.50	0.15	41	3.1	35	50	5	38	AS7-5659a
M-07-51	X09936	171	173	0.80	0.22	27	3.2	0.1	26	0.1	63	AS7-5659a
M-07-51	X09937	173	175	0.43	0.14	44	2.6	0.1	22	10	67	AS7-5662a
M-07-51	X09938	175	177	0.93	0.28	25	2.8	10	26	10	47	AS7-5662a
M-07-51	X09939	177	179	1.23	0.44	16	3.8	0.1	28	5	44	AS7-5662a
M-07-51	X09940	179	181	1.00	0.36	11	3.3	0.1	26	10	39	AS7-5662a
M-07-51	X09941	181	183	0.73	0.23	14	2	0.1	30	15	49	AS7-5662a
M-07-51	X09942	183	185	0.45	0.21	31	2.1	10	36	10	47	AS7-5662a
M-07-51	X09943	185	187	0.45	0.20	18	0.6	20	34	15	38	AS7-5662a
M-07-51	X09944	187	189	0.33	0.16	32	0.7	15	28	10	51	AS7-5662a
M-07-51	X09945	189	191	0.56	0.22	15	2.7	10	28	20	46	AS7-5662a
M-07-51	X09946	191	193	0.92	0.13	12	3.1	20	48	10	45	AS7-5662a
M-07-51	X09947	193	195	0.37	0.10	19	1.4	0.1	38	25	39	AS7-5662a
M-07-51	X09948	195	197	0.74	0.11	26	2.3	25	122	15	98	AS7-5662a
M-07-51	X09950	197	199	0.76	0.27	20	3.3	15	42	20	55	AS7-5662a
M-07-51	X09951	199	201	0.53	0.19	21	2.7	10	70	5	52	AS7-5662a
M-07-51	X09952	201	203	0.75	0.31	38	5.4	35	4098	15	4304	AS7-5662a
M-07-51	X09954	203	205	0.51	0.21	23	3.4	35	1362	0.1	1430	AS7-5662a
M-07-51	X09955	205	207	0.72	0.50	11	4.3	0.1	58	10	49	AS7-5662a
M-07-51	X09956	207	209	0.46	0.14	10	1.1	0.1	30	15	56	AS7-5662a
M-07-51	X09958	209	211	0.38	0.12	13	1.3	5	26	15	47	AS7-5662a
M-07-51	X09959	211	213	0.36	0.16	22	1.4	5	30	15	47	AS7-5662a
M-07-51	X09960	213	215	0.29	0.12	21	1.4	0.1	26	10	40	AS7-5662a
M-07-51	X09961	215	217	0.40	0.18	11	1.4	15	30	0.1	39	AS7-5662a
M-07-51	X09962	217	219	0.79	0.36	26	2.7	0.1	34	20	57	AS7-5662a
M-07-51	X09963	219	221	0.46	0.13	13	1	0.1	56	15	38	AS7-5662a
M-07-51	X09964	221	223	0.32	0.09	10	0.9	0.1	30	20	45	AS7-5662a
M-07-51	X09965	223	225	0.34	0.10	9	0.7	5	28	15	37	AS7-5662a
M-07-51	X09966	225	227	0.47	0.13	13	1.1	0.1	36	5	34	AS7-5662a
M-07-51	X09967	227	229	0.54	0.14	12	1	0.1	26	20	41	AS7-5662a
M-07-51	X09968	229	231	1.20	0.42	12	3.1	5	38	5	39	AS7-5662a
M-07-51	X09969	231	233	1.88	0.65	16	4.4	0.1	40	40	60	AS7-5662a
M-07-51	X09970	233	235	0.71	0.28	13	2	0.1	36	15	45	AS7-5662a
M-07-51	X09971	235	237	0.38	0.15	11	1.9	10	192	10	420	AS7-5662a
M-07-51	X09972	237	239	0.30	0.12	13	1.1	10	26	15	43	AS7-5663a
M-07-51	X09973	239	241	0.56	0.17	14	1.1	0.1	28	15	43	AS7-5663a
M-07-51	X09974	241	243	0.58	0.21	16	1.2	0.1	36	0.1	38	AS7-5663a
M-07-51	X09975	243	245	0.83	0.32	15	2	5	32	10	45	AS7-5663a
M-07-51	X09976	245	247	1.49	0.28	12	2	0.1	34	15	48	AS7-5663a
M-07-51	X09977	247	249	0.51	0.19	22	1.4	15	30	10	62	AS7-5663a
M-07-51	X09978	249	251	2.22	0.74	18	5.3	0.1	28	15	62	AS7-5663a
M-07-51	X09979	251	253	0.47	0.23	30	1.6	0.1	26	25	59	AS7-5663a
M-07-51	X09980	253	255	0.39	0.15	17	1.2	5	30	15	60	AS7-5663a
M-07-51	X09981	255	256.5	0.26	0.12	14	0.8	10	32	10	53	AS7-5663a
M-07-51	X09982	256.5	258	0.33	0.16	12	1.2	0.1	32	10	64	AS7-5663a
M-07-51	X09983	258	259.7	0.35	0.16	16	1.2	5	30	5	79	AS7-5663a
M-07-51	X09984	259.7	261	0.07	0.04	42	0.3	15	46	15	70	AS7-5663a
M-07-51	X09985	261	263	0.00	0.01	7	0.01	30	66	40	59	AS7-5663a
M-07-51	X09987	263	265	0.00	0.01	4	0.01	35	68	30	49	AS7-5663a
M-07-51	X09988	265	266.4	0.00	0.01	10	0.01	35	86	50	54	AS7-5663a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-51	X09989	266.4	268	0.42	0.22	14	1.4	10	32	15	72	AS7-5663a
M-07-51	X09990	268	270	0.72	0.19	22	1.8	15	44	10	84	AS7-5663a
M-07-51	X09992	270	272	0.21	0.14	21	1.3	10	38	20	68	AS7-5663a
M-07-51	X09993	272	274	0.51	0.26	26	1.9	10	40	15	75	AS7-5663a
M-07-51	X09994	274	276	0.48	0.17	31	1.2	15	26	15	64	AS7-5663a
M-07-51	X09995	276	277.9	0.46	0.19	29	1.3	20	32	10	62	AS7-5663a
M-07-51	X09996	277.9	280	0.37	0.21	26	1.4	5	34	10	38	AS7-5663a
M-07-51	X09997	280	282	0.46	0.16	19	1.2	10	30	10	49	AS7-5663a
M-07-51	X09998	282	284	0.35	0.16	50	1.4	10	48	10	63	AS7-5663a
M-07-51	X09999	284	286	0.27	0.14	23	1.7	15	34	10	51	AS7-5663a
M-07-51	X10000	286	288	4.70	0.10	27	4.6	15	54	25	81	AS7-5663a
M-07-51	X10001	288	290	0.35	0.16	32	1.4	15	32	10	44	AS7-5663a
M-07-51	X10002	290	292	1.13	0.31	26	2.4	20	36	10	42	AS7-5663a
M-07-51	X10003	292	294	0.36	0.17	39	1.7	15	38	10	76	AS7-5663a
M-07-51	X10004	294	296	0.27	0.11	37	1	10	48	10	76	AS7-5663a
M-07-51	X10005	296	298	0.28	0.14	43	1.5	0.1	56	10	91	AS7-5663a
M-07-51	X10006	298	300	0.29	0.14	68	3.3	15	536	10	769	AS7-5663a
M-07-51	X10007	300	302	0.28	0.14	48	3.8	20	198	0.1	349	AS7-5664a
M-07-51	X10008	302	304	0.28	0.13	36	1.4	10	62	0.1	78	AS7-5664a
M-07-51	X10009	304	306	0.26	0.12	23	1.1	15	34	0.1	49	AS7-5664a
M-07-51	X10010	306	308	0.32	0.12	62	1.1	10	14	0.1	57	AS7-5664a
M-07-51	X10011	308	310	0.27	0.11	41	0.9	10	14	0.1	55	AS7-5664a
M-07-51	X10012	310	312	0.21	0.08	63	0.7	10	12	0.1	57	AS7-5664a
M-07-51	X10013	312	314	0.18	0.09	40	0.6	10	18	0.1	69	AS7-5664a
M-07-51	X10014	314	316	0.13	0.06	46	1	10	22	0.1	73	AS7-5664a
M-07-51	X10015	316	318	0.31	0.15	34	1.3	10	18	0.1	76	AS7-5664a
M-07-51	X10016	318	320	0.16	0.06	54	0.5	10	10	0.1	82	AS7-5664a
M-07-51	X10018	320	322	0.22	0.12	76	1.3	20	76	0.1	81	AS7-5664a
M-07-51	X10019	322	324	0.28	0.10	46	1.2	20	50	0.1	270	AS7-5664a
M-07-51	X10020	324	326	0.29	0.15	137	1.5	15	16	0.1	125	AS7-5664a
M-07-51	X10021	326	328	0.20	0.11	176	3.4	15	92	0.1	81	AS7-5664a
M-07-51	X10022	328	330	0.26	0.14	73	2.2	15	22	0.1	110	AS7-5664a
M-07-51	X10023	330	332	0.34	0.13	102	1.8	15	28	0.1	99	AS7-5664a
M-07-51	X10024	332	334	0.48	0.14	105	1.7	15	22	0.1	76	AS7-5664a
M-07-51	X10025	334	336	1.88	0.24	59	3	20	56	0.1	141	AS7-5664a
M-07-51	X10026	336	338	0.48	0.11	123	1.7	25	138	0.1	140	AS7-5664a
M-07-51	X10027	338	340	0.47	0.17	411	2.1	20	24	0.1	105	AS7-5664a
M-07-51	X10028	340	342	0.28	0.11	145	1.3	10	10	0.1	82	AS7-5664a
M-07-51	X10029	342	344	0.36	0.11	137	1.1	10	14	0.1	83	AS7-5664a
M-07-51	X10030	344	346	0.47	0.14	276	1.4	10	198	0.1	124	AS7-5664a
M-07-51	X10031	346	348	0.53	0.14	79	2.4	25	38	0.1	109	AS7-5664a
M-07-51	X10032	348	350	0.72	0.21	611	3.2	25	54	0.1	120	AS7-5664a
M-07-51	X10033	350	352	0.48	0.16	411	2.3	15	798	0.1	70	AS7-5664a
M-07-51	X10034	352	354	0.39	0.16	116	2.1	15	98	0.1	70	AS7-5664a
M-07-51	X10035	354	356	0.26	0.12	243	1.8	15	30	0.1	103	AS7-5664a
M-07-51	X10037	356	358	0.34	0.11	145	2	15	36	0.1	91	AS7-5664a
M-07-51	X10038	358	360	0.22	0.09	42	1.5	15	10	0.1	75	AS7-5664a
M-07-51	X10040	360	362	1.24	0.31	444	4.1	15	58	0.1	140	AS7-5664a
M-07-51	X10041	362	364	0.31	0.11	117	1.5	15	12	0.1	72	AS7-5664a
M-07-51	X10042	364	366	0.20	0.13	87	1.5	0.1	26	10	48	AS7-5666a
M-07-51	X10043	366	368	0.16	0.06	92	0.8	10	48	5	58	AS7-5666a
M-07-51	X10044	368	370	0.31	0.11	95	1.6	10	38	10	62	AS7-5666a
M-07-51	X10045	370	372	0.33	0.14	105	1.8	10	32	5	89	AS7-5666a
M-07-51	X10046	372	374	0.64	0.28	215	4.9	5	30	10	57	AS7-5666a
M-07-51	X10047	374	376	0.22	0.07	242	2.3	0.1	28	5	28	AS7-5666a
M-07-51	X10048	376	378	0.24	0.10	67	2.3	5	32	10	92	AS7-5666a
M-07-51	X10049	378	380	0.15	0.10	62	1.4	10	36	0.1	65	AS7-5666a
M-07-51	X10050	380	382	0.19	0.09	164	1	10	32	5	57	AS7-5666a
M-07-51	X10051	382	384	0.45	0.15	129	1.9	20	30	5	45	AS7-5666a
M-07-51	X10052	384	386	0.38	0.15	64	1.8	0.1	30	25	63	AS7-5666a
M-07-51	X10053	386	388	0.20	0.09	78	1.3	10	32	5	46	AS7-5666a
M-07-51	X10054	388	390	0.23	0.08	80	1.5	10	48	5	77	AS7-5666a
M-07-51	X10055	390	392	0.12	0.07	56	0.9	0.1	32	5	44	AS7-5666a
M-07-51	X10056	392	394	0.20	0.09	102	1.1	10	40	5	40	AS7-5666a
M-07-51	X10057	394	396	0.42	0.10	101	2.5	25	46	10	92	AS7-5666a
M-07-51	X10058	396	398	0.23	0.09	66	3.3	15	54	0.1	165	AS7-5666a
M-07-51	X10059	398	400	0.23	0.10	53	1.4	5	38	10	78	AS7-5666a
M-07-51	X10060	400	402	0.38	0.13	78	2.6	20	36	0.1	69	AS7-5666a
M-07-51	X10061	402	404	0.23	0.11	320	1.7	10	26	5	73	AS7-5666a
M-07-51	X10062	404	406	0.15	0.06	39	0.7	5	32	5	48	AS7-5666a
M-07-51	X10063	406	408	0.13	0.06	57	0.6	5	22	15	51	AS7-5666a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-51	X10064	408	410	0.31	0.06	46	1.1	0.1	30	0.1	47	AS7-5666a
M-07-51	X10065	410	412	0.35	0.08	91	1.5	5	40	10	71	AS7-5666a
M-07-51	X10066	412	414	0.28	0.19	92	2.9	15	46	10	91	AS7-5666a
M-07-51	X10067	414	416	0.45	0.18	106	2.3	0.1	42	5	58	AS7-5666a
M-07-51	X10068	416	418	0.37	0.15	63	1.8	15	44	10	116	AS7-5666a
M-07-51	X10070	418	420	0.36	0.13	40	1.8	5	38	10	92	AS7-5666a
M-07-51	X10072	420	422	0.18	0.07	94	0.9	0.1	40	10	94	AS7-5666a
M-07-51	X10073	422	424	0.25	0.10	365	1	15	40	15	96	AS7-5666a
M-07-51	X10075	424	426	0.15	0.07	97	1.3	5	44	5	110	AS7-5666a
M-07-51	X10076	426	428	0.19	0.08	58	0.9	10	40	15	68	AS7-5666a
M-07-51	X10077	428	430	0.46	0.13	73	2.1	0.1	34	25	72	AS7-5680a
M-07-51	X10078	430	431.57	0.20	0.13	47	1.6	0.1	34	15	91	AS7-5680a
M-07-52	X05374	1.5	5	0.89	0.16	69	0.2	10	58	10	213	AS7-5667a
M-07-52	X05375	5	6	1.02	0.19	140	1.6	0.1	44	0.1	336	AS7-5667a
M-07-52	X05376	6	8	0.80	0.16	152	1.8	0.1	80	0.1	209	AS7-5667a
M-07-52	X05377	8	10	0.78	0.16	77	1.8	0.1	102	0.1	471	AS7-5667a
M-07-52	X05378	10	12.1	0.97	0.17	92	2	0.1	176	0.1	700	AS7-5668a
M-07-52	X05379	13.7	16	0.76	0.14	39	1.8	0.1	138	0.1	254	AS7-5668a
M-07-52	X05380	16	18	0.65	0.17	32	1.4	0.1	40	0.1	242	AS7-5668a
M-07-52	X05381	18	20	0.69	0.20	25	1.6	0.1	30	0.1	195	AS7-5668a
M-07-52	X05382	20	22	0.41	0.12	15	0.9	0.1	38	0.1	233	AS7-5668a
M-07-52	X05383	22	24	0.55	0.12	13	1.1	0.1	224	0.1	231	AS7-5668a
M-07-52	X05384	24	26	0.54	0.15	15	0.9	0.1	32	10	411	AS7-5668a
M-07-52	X05385	26	28	0.60	0.14	131	1.6	0.1	48	0.1	110	AS7-5668a
M-07-52	X05386	28	30	0.81	0.15	81	1.5	0.1	100	0.1	314	AS7-5668a
M-07-52	X05387	30	32	1.12	0.21	83	2.8	165	144	75	606	AS7-5668a
M-07-52	X05388	32	34	1.13	0.21	60	1.9	0.1	176	0.1	607	AS7-5668a
M-07-52	X05389	34	36.1	1.00	0.21	64	1.7	0.1	148	0.1	438	AS7-5668a
M-07-52	X05390	36.1	41.1	1.12	0.18	479	1.7	10	166	0.1	252	AS7-5668a
M-07-52	X05391	41.1	43	0.91	0.13	68	1.4	0.1	108	0.1	139	AS7-5668a
M-07-52	X05392	43	45	0.89	0.15	77	1.8	0.1	108	0.1	301	AS7-5668a
M-07-52	X05393	45	47	0.76	0.18	71	2.2	30	100	15	355	AS7-5668a
M-07-52	X05394	47	49	0.94	0.16	77	1.8	40	62	0.1	134	AS7-5668a
M-07-52	X05395	49	51	0.91	0.18	86	1.4	15	56	0.1	212	AS7-5668a
M-07-52	X05396	51	53	0.51	0.16	82	0.8	45	52	0.1	170	AS7-5668a
M-07-52	X05397	53	55	1.19	0.20	95	1.2	30	48	0.1	199	AS7-5668a
M-07-52	X05398	55	57	1.04	0.18	109	1	20	54	0.1	133	AS7-5668a
M-07-52	X05399	57	59	0.98	0.20	93	0.8	25	48	0.1	137	AS7-5668a
M-07-52	X05401	59	61	0.90	0.17	137	1.1	30	36	0.1	121	AS7-5668a
M-07-52	X05402	61	63	0.99	0.18	89	2.1	30	118	5	485	AS7-5668a
M-07-52	X05403	63	65	0.57	0.15	57	1.2	0.1	142	0.1	366	AS7-5668a
M-07-52	X05405	65	67	0.66	0.11	57	0.8	20	98	0.1	101	AS7-5668a
M-07-52	X05406	67	69	0.58	0.19	83	1.6	35	80	10	167	AS7-5668a
M-07-52	X05407	69	71	1.03	0.17	105	1.5	0.1	88	0.1	249	AS7-5668a
M-07-52	X05409	71	73	1.03	0.15	127	1	0.1	52	0.1	413	AS7-5668a
M-07-52	X05410	73	75	0.74	0.17	101	1.1	0.1	104	0.1	211	AS7-5668a
M-07-52	X05411	75	77	0.89	0.17	105	1.1	5	42	0.1	84	AS7-5668a
M-07-52	X05412	77	79	1.18	0.19	160	1.3	0.1	72	0.1	140	AS7-5668a
M-07-52	X05413	79	81	0.97	0.15	102	1.2	0.1	48	0.1	100	AS7-5669a
M-07-52	X05414	81	83	0.92	0.15	83	1.4	0.1	92	0.1	257	AS7-5669a
M-07-52	X05415	83	85	1.22	0.21	137	1.4	10	54	0.1	212	AS7-5669a
M-07-52	X05416	85	87	0.48	0.11	111	1	25	58	10	352	AS7-5669a
M-07-52	X05417	87	89	0.76	0.15	122	1.9	70	146	0.1	910	AS7-5669a
M-07-52	X05418	89	91	0.52	0.12	125	1.3	45	84	0.1	90	AS7-5669a
M-07-52	X05419	91	93	0.38	0.13	80	1.1	155	76	20	113	AS7-5669a
M-07-52	X05420	93	94.65	0.47	0.14	109	1.4	375	92	20	95	AS7-5669a
M-07-52	X05421	94.65	96.05	0.41	0.14	77	1.7	110	124	35	70	AS7-5669a
M-07-52	X05422	96.05	98.3	0.00	0.00	8	0.2	40	112	5	269	AS7-5669a
M-07-52	X05423	98.3	100	2.07	0.18	89	2.5	20	46	0.1	1697	AS7-5669a
M-07-52	X05424	100	102	0.87	0.18	62	2.1	40	42	15	83	AS7-5669a
M-07-52	X05425	102	104	0.44	0.15	81	1.6	50	56	45	36	AS7-5669a
M-07-52	X05426	104	106	0.62	0.20	75	1.6	40	34	45	49	AS7-5669a
M-07-52	X05427	106	108	1.11	0.22	78	2.3	55	54	65	68	AS7-5669a
M-07-52	X05428	108	110	0.58	0.16	62	1.6	55	86	50	45	AS7-5669a
M-07-52	X05429	110	112	0.31	0.14	101	1.4	25	52	25	24	AS7-5669a
M-07-52	X05430	112	114	0.42	0.16	77	1.6	30	40	25	42	AS7-5669a
M-07-52	X05431	114	116	0.91	0.18	104	1.4	15	60	5	47	AS7-5669a
M-07-52	X05432	116	118	0.90	0.21	110	1.5	20	40	15	67	AS7-5669a
M-07-52	X05433	118	120	2.07	0.16	302	1.3	25	32	10	163	AS7-5669a
M-07-52	X05434	120	122	0.72	0.18	77	1.4	15	18	10	24	AS7-5669a
M-07-52	X05435	122	124	0.94	0.17	92	1.3	20	28	5	23	AS7-5669a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-52	X05436	124	126	1.19	0.27	146	2.3	35	28	15	41	AS7-5669a
M-07-52	X05437	126	128	0.73	0.25	194	2.2	10	26	0.1	26	AS7-5669a
M-07-52	X05438	128	130	1.03	0.19	187	1.7	10	34	0.1	18	AS7-5669a
M-07-52	X05439	130	132	0.84	0.18	96	1.4	20	50	0.1	66	AS7-5669a
M-07-52	X05440	132	134	0.37	0.16	73	1.1	10	52	0.1	38	AS7-5669a
M-07-52	X05441	134	136	0.33	0.22	62	1.3	5	70	0.1	103	AS7-5669a
M-07-52	X05444	136	138	0.50	0.13	57	1.3	15	138	0.1	21	AS7-5669a
M-07-52	X05445	138	140	0.68	0.17	48	1.4	25	38	0.1	53	AS7-5669a
M-07-52	X05446	140	142	0.94	0.19	92	1.8	20	48	0.1	24	AS7-5669a
M-07-52	X05447	142	144	0.85	0.21	75	2	15	138	0.1	394	AS7-5669a
M-07-52	X05448	144	146	0.65	0.13	72	1.5	35	104	0.1	286	AS7-5670a
M-07-52	X05449	146	148	0.44	0.05	112	0.9	35	76	0.1	167	AS7-5670a
M-07-52	X05450	148	150	0.66	0.14	88	1.3	45	42	10	54	AS7-5670a
M-07-52	X05451	150	152	0.91	0.20	72	1.7	25	36	5	319	AS7-5670a
M-07-52	X05452	152	154	1.22	0.19	77	1.8	15	52	0.1	94	AS7-5670a
M-07-52	X05453	154	156	0.51	0.16	85	2.4	70	46	5	51	AS7-5670a
M-07-52	X05455	156	158	0.50	0.23	90	2.1	25	42	20	35	AS7-5670a
M-07-52	X05456	158	160	1.07	0.19	164	2.5	40	38	0.1	71	AS7-5670a
M-07-52	X05457	160	162	1.20	0.18	63	1.9	20	32	0.1	60	AS7-5670a
M-07-52	X05458	162	164	0.85	0.15	104	1.4	10	44	0.1	56	AS7-5670a
M-07-52	X05459	164	166	0.77	0.14	44	1.8	10	32	0.1	44	AS7-5670a
M-07-52	X05460	166	168	0.62	0.14	62	1.4	0.1	32	0.1	19	AS7-5670a
M-07-52	X05461	168	170	0.63	0.18	43	1.8	15	44	0.1	43	AS7-5670a
M-07-52	X05462	170	172	0.90	0.15	67	2.2	30	34	0.1	22	AS7-5670a
M-07-52	X05463	172	174	0.88	0.17	79	1.8	20	28	0.1	33	AS7-5670a
M-07-52	X05464	174	176	0.89	0.18	41	2.3	10	28	0.1	33	AS7-5670a
M-07-52	X05465	176	178	0.67	0.15	57	2.1	15	34	0.1	46	AS7-5670a
M-07-52	X05466	178	180	0.81	0.19	40	2.7	0.1	28	0.1	37	AS7-5670a
M-07-52	X05467	180	182	0.61	0.16	34	2.2	10	30	0.1	34	AS7-5670a
M-07-52	X05469	182	184	0.44	0.13	80	1.8	10	30	0.1	53	AS7-5670a
M-07-52	X05470	184	186	0.43	0.14	51	2.1	0.1	34	0.1	33	AS7-5670a
M-07-52	X05471	186	188	0.35	0.09	63	2.5	5	44	0.1	36	AS7-5670a
M-07-52	X05472	188	190	0.41	0.12	46	3.2	0.1	68	0.1	57	AS7-5670a
M-07-52	X05474	190	192	0.80	0.15	109	5.1	10	76	0.1	21	AS7-5670a
M-07-52	X05475	192	194	0.58	0.14	64	5.3	0.1	98	0.1	75	AS7-5670a
M-07-52	X05476	194	196	0.79	0.20	36	5	0.1	40	15	35	AS7-5670a
M-07-52	X05477	196	198	0.58	0.16	37	5.5	10	62	0.1	45	AS7-5670a
M-07-52	X05478	198	200	0.73	0.20	65	3.3	10	48	0.1	49	AS7-5670a
M-07-52	X05479	200	202	0.66	0.12	71	1.9	10	62	10	227	AS7-5670a
M-07-52	X05480	202	204	0.48	0.14	57	3.3	0.1	98	0.1	130	AS7-5670a
M-07-52	X05481	204	206	0.45	0.14	65	5.5	0.1	86	0.1	55	AS7-5670a
M-07-52	X05482	206	208	0.29	0.09	53	2.4	0.1	76	10	132	AS7-5670a
M-07-52	X05483	208	210.31	0.36	0.11	59	16.4	0.1	62	0.1	77	AS7-5671a
M-07-52	X05484	211.75	214	0.36	0.10	59	1.8	0.1	52	5	81	AS7-5671a
M-07-52	X05485	214	216	0.37	0.10	56	1.7	5	60	0.1	60	AS7-5671a
M-07-52	X05486	216	218	0.36	0.10	57	1.5	10	68	10	93	AS7-5671a
M-07-52	X05487	218	220	0.21	0.08	33	1.3	5	52	5	82	AS7-5671a
M-07-52	X05488	220	222	0.13	0.07	36	1.3	0.1	50	0.1	48	AS7-5671a
M-07-52	X05489	222	224	0.14	0.06	76	1.2	0.1	56	0.1	31	AS7-5671a
M-07-52	X05490	224	226	0.28	0.10	57	2	10	68	10	81	AS7-5671a
M-07-52	X05491	226	228	0.63	0.13	40	2.1	15	72	10	140	AS7-5671a
M-07-52	X05492	228	230	0.38	0.09	38	1.5	10	72	10	130	AS7-5671a
M-07-52	X05493	230	232	0.31	0.08	48	1.2	10	96	5	113	AS7-5671a
M-07-52	X05494	232	234	0.27	0.09	53	1	0.1	120	0.1	152	AS7-5671a
M-07-52	X05495	234	236	0.23	0.08	54	1.1	5	102	0.1	113	AS7-5671a
M-07-52	X05496	236	238	0.35	0.08	53	0.7	15	60	10	118	AS7-5671a
M-07-52	X05497	238	240	0.28	0.08	51	0.8	0.1	110	0.1	159	AS7-5671a
M-07-52	X05498	240	242	0.26	0.10	39	0.7	0.1	44	0.1	79	AS7-5671a
M-07-52	X05499	242	244	0.40	0.13	34	0.9	0.1	36	0.1	51	AS7-5671a
M-07-52	X05500	244	246	0.35	0.12	66	1.1	0.1	46	0.1	51	AS7-5671a
M-07-52	X05501	246	248	0.51	0.12	129	0.9	0.1	42	0.1	41	AS7-5671a
M-07-52	X05502	248	250	0.38	0.10	53	1.1	0.1	40	0.1	37	AS7-5671a
M-07-52	X05503	250	251.46	0.32	0.08	20	0.7	0.1	62	0.1	31	AS7-5671a
M-07-52	X05504	251.46	252.3	0.42	0.10	60	1.1	0.1	68	0.1	78	AS7-5671a
M-07-52	X05505	252.3	254	0.33	0.08	85	0.9	0.1	60	0.1	72	AS7-5671a
M-07-52	X05506	254	256	0.45	0.13	40	1.1	0.1	56	0.1	71	AS7-5671a
M-07-52	X05507	256	258	0.42	0.13	50	1	0.1	38	0.1	39	AS7-5671a
M-07-52	X05508	258	260	0.43	0.08	74	0.9	0.1	32	0.1	62	AS7-5671a
M-07-52	X05509	260	262	0.35	0.10	33	1	5	58	0.1	73	AS7-5671a
M-07-52	X05510	262	264	0.51	0.10	43	0.8	0.1	44	10	59	AS7-5671a
M-07-52	X05511	264	266	0.26	0.10	42	2.6	50	78	85	77	AS7-5671a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-52	X05514	266	268	0.42	0.11	52	0.9	0.1	58	0.1	42	AS7-5671a
M-07-52	X05515	268	270	0.24	0.09	57	0.7	15	66	10	106	AS7-5671a
M-07-52	X05516	270	272	0.34	0.05	69	0.5	10	56	15	139	AS7-5671a
M-07-52	X05517	272	274	0.19	0.07	59	0.6	0.1	44	5	31	AS7-5671a
M-07-52	X05518	274	276	0.23	0.07	67	0.4	0.1	36	10	28	AS7-5682a
M-07-52	X05519	276	278	0.31	0.10	47	0.9	0.1	38	20	50	AS7-5682a
M-07-52	X05520	278	280	0.28	0.06	58	0.4	0.1	42	15	78	AS7-5682a
M-07-52	X05521	280	282	0.30	0.10	96	0.7	0.1	50	15	57	AS7-5682a
M-07-52	X05522	282	284	0.19	0.09	49	3.4	25	68	60	58	AS7-5682a
M-07-52	X05523	284	286	0.27	0.07	53	0.7	0.1	48	10	58	AS7-5682a
M-07-52	X05524	286	288	0.34	0.13	35	1.2	0.1	116	5	36	AS7-5682a
M-07-52	X05525	288	290	0.48	0.07	134	1.7	5	52	20	96	AS7-5682a
M-07-52	X05526	290	292	0.34	0.09	68	1.2	0.1	42	15	51	AS7-5682a
M-07-52	X05527	292	294	0.39	0.10	73	1.4	0.1	56	10	42	AS7-5682a
M-07-52	X05528	294	296	0.35	0.08	102	2.1	10	44	25	67	AS7-5682a
M-07-52	X05529	296	298	0.41	0.08	108	3.3	0.1	64	15	47	AS7-5682a
M-07-52	X05530	298	300	0.47	0.18	92	1.8	0.1	32	10	46	AS7-5682a
M-07-52	X05531	300	302	0.44	0.14	40	1.4	0.1	42	5	61	AS7-5682a
M-07-52	X05533	302	304	0.33	0.08	76	0.9	0.1	62	10	50	AS7-5682a
M-07-52	X05534	304	306	0.32	0.07	77	0.9	0.1	50	10	66	AS7-5682a
M-07-52	X05535	306	308	0.44	0.08	55	0.7	10	52	0.1	41	AS7-5682a
M-07-52	X05536	308	310	0.40	0.07	58	1	10	44	25	75	AS7-5682a
M-07-52	X05537	310	312	0.30	0.05	56	0.5	0.1	40	20	53	AS7-5682a
M-07-52	X05538	312	314	0.38	0.11	67	1.1	0.1	44	5	33	AS7-5682a
M-07-52	X05539	314	316	0.34	0.10	112	0.9	0.1	38	30	36	AS7-5682a
M-07-52	X05542	316	318	0.52	0.12	96	1	0.1	34	15	60	AS7-5682a
M-07-52	X05543	318	320	0.47	0.11	71	0.9	0.1	46	10	50	AS7-5682a
M-07-52	X05544	320	322	0.57	0.14	65	1	0.1	60	0.1	42	AS7-5682a
M-07-52	X05545	322	324	0.21	0.09	48	0.8	0.1	52	0.1	50	AS7-5682a
M-07-52	X05546	324	326	0.30	0.08	71	0.7	0.1	58	10	74	AS7-5682a
M-07-52	X05547	326	328	0.21	0.06	43	1	5	42	0.1	37	AS7-5682a
M-07-52	X05548	328	330	0.28	0.09	137	0.9	0.1	52	0.1	62	AS7-5682a
M-07-52	X05549	330	332	0.59	0.09	78	1.1	0.1	66	15	72	AS7-5682a
M-07-52	X05550	332	334	0.15	0.07	51	0.7	0.1	40	25	39	AS7-5682a
M-07-52	X05551	334	336	0.23	0.07	71	0.4	0.1	42	10	40	AS7-5682a
M-07-52	X05552	336	338	0.20	0.07	83	0.6	0.1	42	10	26	AS7-5682a
M-07-52	X05553	338	340	0.19	0.05	46	0.2	10	10	0.1	30	AS7-5705a
M-07-52	X05554	340	342	0.17	0.05	23	0.3	10	14	0.1	39	AS7-5705a
M-07-52	X05555	342	344	0.19	0.06	40	0.4	10	12	0.1	33	AS7-5705a
M-07-52	X05556	344	346	0.32	0.10	28	0.9	10	18	0.1	20	AS7-5705a
M-07-52	X05557	346	348	0.22	0.07	20	0.4	10	12	0.1	48	AS7-5705a
M-07-52	X05558	348	350	0.32	0.07	98	0.5	10	14	0.1	26	AS7-5705a
M-07-52	X05559	350	352	0.33	0.07	60	0.3	10	10	0.1	18	AS7-5705a
M-07-52	X05560	352	354	0.33	0.07	53	0.2	15	14	0.1	23	AS7-5705a
M-07-52	X05561	354	356	0.34	0.08	146	0.7	15	28	0.1	64	AS7-5705a
M-07-52	X05562	356	358	0.28	0.07	50	0.6	15	50	0.1	59	AS7-5705a
M-07-52	X05563	358	360	0.21	0.05	37	0.01	15	20	0.1	39	AS7-5705a
M-07-52	X05564	360	362	0.21	0.05	79	0.3	15	18	0.1	26	AS7-5705a
M-07-52	X05565	362	364	0.28	0.05	29	0.4	15	12	0.1	38	AS7-5705a
M-07-52	X05566	364	366	0.26	0.06	58	0.5	15	8	0.1	46	AS7-5705a
M-07-52	X05567	366	368	0.34	0.09	69	0.8	15	36	0.1	159	AS7-5705a
M-07-52	X05568	368	370	0.25	0.06	41	0.5	15	10	0.1	45	AS7-5705a
M-07-52	X05569	370	372	0.24	0.05	56	0.3	10	20	0.1	26	AS7-5705a
M-07-52	X05570	372	374	0.18	0.05	131	0.4	15	20	0.1	45	AS7-5705a
M-07-52	X05571	374	376	0.17	0.04	90	0.4	15	20	0.1	38	AS7-5705a
M-07-52	X05572	376	378	0.24	0.06	73	0.6	20	14	0.1	70	AS7-5705a
M-07-52	X05573	378	378.87	0.31	0.06	57	0.4	15	14	0.1	42	AS7-5705a
M-07-53	X12001	4.6	6	0.31	0.08	128	1.8	15	56	0.1	54	AS7-5672a
M-07-53	X12002	6	8	0.52	0.12	93	1.9	10	38	0.1	36	AS7-5672a
M-07-53	X12003	8	10	0.18	0.05	65	0.9	15	50	10	32	AS7-5672a
M-07-53	X12004	10	12	0.16	0.04	31	1.1	0.1	58	15	72	AS7-5672a
M-07-53	X12005	12	14	0.25	0.08	45	3	0.1	188	0.1	95	AS7-5672a
M-07-53	X12006	14	16	0.15	0.06	41	3	10	78	0.1	109	AS7-5672a
M-07-53	X12007	16	18	0.20	0.07	30	2.3	20	66	10	133	AS7-5672a
M-07-53	X12008	18	20	0.12	0.04	24	1.3	10	36	10	72	AS7-5672a
M-07-53	X12009	20	22	0.23	0.05	43	1.7	20	44	15	114	AS7-5672a
M-07-53	X12010	22	24	0.25	0.11	80	3.7	15	48	0.1	75	AS7-5672a
M-07-53	X12011	24	26	0.31	0.10	127	3.4	15	36	10	91	AS7-5672a
M-07-53	X12012	26	28	0.43	0.20	44	7.3	10	118	20	67	AS7-5672a
M-07-53	X12013	28	30	0.54	0.14	37	3.5	20	70	10	116	AS7-5672a
M-07-53	X12014	30	32	0.35	0.10	50	3.5	15	94	15	169	AS7-5672a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-53	X12015	32	34	0.24	0.06	32	2	10	52	10	134	AS7-5672a
M-07-53	X12016	34	36	0.38	0.10	27	3.3	0.1	64	5	157	AS7-5672a
M-07-53	X12017	36	38	0.33	0.08	37	2.6	10	56	10	145	AS7-5672a
M-07-53	X12018	38	40	0.60	0.19	59	11.2	10	310	5	431	AS7-5672a
M-07-53	X12019	40	42	0.52	0.13	43	6.2	15	190	0.1	1033	AS7-5672a
M-07-53	X12020	42	44	0.47	0.13	40	5.4	25	142	0.1	174	AS7-5672a
M-07-53	X12021	44	46	0.42	0.16	60	13.5	15	754	10	748	AS7-5672a
M-07-53	X12022	46	48	0.40	0.12	42	3.6	0.1	64	0.1	117	AS7-5672a
M-07-53	X12023	48	50	0.31	0.08	25	1.7	5	42	0.1	124	AS7-5672a
M-07-53	X12024	50	52	0.20	0.07	30	1.6	10	122	0.1	124	AS7-5672a
M-07-53	X12025	52	54	0.44	0.10	72	1.9	20	48	5	87	AS7-5672a
M-07-53	X12026	54	56	0.30	0.10	47	1.6	10	42	10	90	AS7-5672a
M-07-53	X12027	56	58	0.51	0.16	52	2.7	15	52	15	104	AS7-5672a
M-07-53	X12028	58	60	0.52	0.11	54	2.2	20	54	10	100	AS7-5672a
M-07-53	X12029	60	62	0.30	0.10	43	1.7	10	60	0.1	102	AS7-5672a
M-07-53	X12031	62	64	0.20	0.07	43	1.3	20	80	5	128	AS7-5672a
M-07-53	X12032	64	66	0.28	0.08	38	1.3	10	48	0.1	80	AS7-5672a
M-07-53	X12033	66	68	0.40	0.10	46	1.7	0.1	38	5	69	AS7-5672a
M-07-53	X12034	68	70	0.51	0.12	38	2	15	46	0.1	78	AS7-5672a
M-07-53	X12036	70	72	0.37	0.13	36	1.9	0.1	38	10	68	AS7-5673a
M-07-53	X12037	72	74	0.31	0.11	33	2.1	0.1	48	0.1	82	AS7-5673a
M-07-53	X12038	74	76	0.44	0.11	40	1.5	0.1	34	0.1	89	AS7-5673a
M-07-53	X12039	76	78	0.26	0.08	39	1.2	0.1	34	0.1	97	AS7-5673a
M-07-53	X12040	78	80	0.36	0.10	29	1.5	0.1	36	0.1	110	AS7-5673a
M-07-53	X12041	80	82	0.29	0.08	32	1.5	0.1	40	0.1	88	AS7-5673a
M-07-53	X12042	82	84	0.44	0.10	34	1.4	0.1	42	0.1	84	AS7-5673a
M-07-53	X12043	84	86	1.10	0.26	47	2.6	0.1	38	5	87	AS7-5673a
M-07-53	X12044	86	88	0.84	0.31	29	4.4	0.1	166	0.1	124	AS7-5673a
M-07-53	X12045	88	90	0.46	0.11	34	1.7	0.1	36	5	75	AS7-5673a
M-07-53	X12046	90	92	0.62	0.18	41	2.7	5	52	0.1	88	AS7-5673a
M-07-53	X12047	92	94	1.78	0.10	30	9.9	0.1	362	0.1	2420	AS7-5673a
M-07-53	X12048	94	96	0.39	0.10	29	1.4	0.1	36	0.1	121	AS7-5673a
M-07-53	X12049	96	98	0.77	0.18	39	2.6	0.1	40	0.1	97	AS7-5673a
M-07-53	X12050	98	100	0.89	0.21	38	2.5	0.1	36	5	70	AS7-5673a
M-07-53	X12051	100	102	0.88	0.24	39	2.6	0.1	42	0.1	76	AS7-5673a
M-07-53	X12052	102	104	0.39	0.12	31	1	0.1	32	0.1	72	AS7-5673a
M-07-53	X12053	104	106	0.96	0.20	42	2.1	0.1	40	0.1	84	AS7-5673a
M-07-53	X12054	106	108	0.90	0.19	49	1.8	0.1	40	0.1	77	AS7-5673a
M-07-53	X12055	108	110	1.31	0.29	21	3.8	0.1	42	0.1	67	AS7-5673a
M-07-53	X12056	110	112	1.05	0.25	23	2.7	0.1	36	5	80	AS7-5673a
M-07-53	X12057	112	114	0.50	0.11	30	1.5	0.1	36	0.1	82	AS7-5673a
M-07-53	X12058	114	116	0.52	0.15	32	1.8	0.1	40	0.1	72	AS7-5673a
M-07-53	X12059	116	118	0.51	0.15	33	1.8	0.1	38	0.1	77	AS7-5673a
M-07-53	X12060	118	120	0.37	0.09	23	1	0.1	34	0.1	104	AS7-5673a
M-07-53	X12061	120	122	0.56	0.14	26	1.5	0.1	44	5	117	AS7-5673a
M-07-53	X12062	122	124	0.28	0.08	17	0.9	0.1	36	0.1	141	AS7-5673a
M-07-53	X12063	124	126	0.35	0.11	29	1.1	0.1	46	0.1	123	AS7-5673a
M-07-53	X12064	126	128	0.47	0.14	27	1.5	0.1	40	0.1	104	AS7-5673a
M-07-53	X12065	128	130	0.29	0.10	34	1.6	0.1	124	10	218	AS7-5673a
M-07-53	X12066	130	132	0.51	0.18	26	1.9	5	52	15	91	AS7-5673a
M-07-53	X12070	132	134	0.66	0.20	23	2.7	5	80	0.1	89	AS7-5673a
M-07-53	X12071	134	136	0.82	0.25	23	7.4	10	76	20	247	AS7-5674a
M-07-53	X12072	136	138	1.05	0.34	20	5.4	0.1	76	25	169	AS7-5674a
M-07-53	X12073	138	140	1.00	0.24	42	2.8	15	74	15	118	AS7-5674a
M-07-53	X12074	140	142	1.17	0.29	23	3.5	0.1	76	25	128	AS7-5674a
M-07-53	X12075	142	144	0.73	0.21	32	3	0.1	52	10	111	AS7-5674a
M-07-53	X12076	144	146	0.60	0.16	25	2.6	0.1	106	15	210	AS7-5674a
M-07-53	X12077	146	148	1.29	0.19	77	4.2	5	76	25	132	AS7-5674a
M-07-53	X12078	148	150	1.76	0.23	51	5.4	55	62	30	102	AS7-5674a
M-07-53	X12079	150	152	1.57	0.24	54	3.3	30	56	10	82	AS7-5674a
M-07-53	X12080	152	154	1.39	0.20	32	4.1	75	56	15	137	AS7-5674a
M-07-53	X12081	154	156	0.85	0.21	50	3.2	0.1	70	25	106	AS7-5674a
M-07-53	X12082	156	158	0.58	0.14	27	2	0.1	50	20	130	AS7-5674a
M-07-53	X12083	158	160	0.49	0.12	30	2.6	0.1	42	20	141	AS7-5674a
M-07-53	X12084	160	162	0.32	0.08	21	1.7	0.1	64	20	156	AS7-5674a
M-07-53	X12085	162	164	0.76	0.22	25	3.2	0.1	48	20	118	AS7-5674a
M-07-53	X12086	164	166	0.58	0.20	32	3	0.1	68	20	187	AS7-5674a
M-07-53	X12087	166	168	0.56	0.19	25	2.9	0.1	64	15	164	AS7-5674a
M-07-53	X12088	168	170	0.36	0.10	20	1.9	0.1	52	25	176	AS7-5674a
M-07-53	X12089	170	172	0.49	0.17	18	2.8	0.1	50	15	179	AS7-5674a
M-07-53	X12091	172	174	0.49	0.16	24	2.8	0.1	58	15	158	AS7-5674a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-53	X12092	174	176	1.05	0.33	30	12.7	0.1	114	50	139	AS7-5674a
M-07-53	X12093	176	178	0.58	0.19	23	4.2	0.1	74	15	139	AS7-5674a
M-07-53	X12094	178	180	0.38	0.15	32	2.8	0.1	68	15	130	AS7-5674a
M-07-53	X12095	180	182	0.88	0.22	29	3.3	0.1	48	15	118	AS7-5674a
M-07-53	X12096	182	184	0.67	0.20	27	2.8	0.1	56	20	142	AS7-5674a
M-07-53	X12097	184	186	1.01	0.34	19	5.3	0.1	54	15	134	AS7-5674a
M-07-53	X12098	186	188	0.87	0.31	20	4.4	0.1	108	15	124	AS7-5674a
M-07-53	X12099	188	190	0.62	0.17	27	2.3	0.1	46	15	102	AS7-5674a
M-07-53	X12101	190	192	0.61	0.18	21	2.9	0.1	60	20	181	AS7-5674a
M-07-53	X12102	192	194	0.51	0.16	23	2.4	0.1	48	20	97	AS7-5674a
M-07-53	X12103	194	196	0.57	0.35	20	5.8	0.1	50	30	82	AS7-5674a
M-07-53	X12104	196	198	0.75	0.20	19	3.3	20	42	5	88	AS7-5674a
M-07-53	X12105	198	200	0.73	0.22	23	4.4	10	44	20	81	AS7-5674a
M-07-53	X12106	200	202	1.08	0.17	30	2.3	10	44	20	83	AS7-5679a
M-07-53	X12107	202	204	0.92	0.26	26	3.3	5	48	20	76	AS7-5679a
M-07-53	X12108	204	206	0.90	0.19	29	2.3	0.1	46	15	82	AS7-5679a
M-07-53	X12109	206	208	1.01	0.26	31	3.6	0.1	34	25	67	AS7-5679a
M-07-53	X12110	208	210	0.95	0.19	26	3.4	5	44	15	65	AS7-5679a
M-07-53	X12111	210	212	0.65	0.13	28	2	10	36	10	85	AS7-5679a
M-07-53	X12112	212	214	0.68	0.16	25	2.3	0.1	38	20	86	AS7-5679a
M-07-53	X12113	214	216	0.96	0.15	25	2.3	5	34	15	80	AS7-5679a
M-07-53	X12114	216	218	0.83	0.16	31	2.5	5	70	30	121	AS7-5679a
M-07-53	X12115	218	220	0.74	0.20	24	2.7	0.1	34	30	101	AS7-5679a
M-07-53	X12116	220	222	1.05	0.21	40	5.8	5	66	30	71	AS7-5679a
M-07-53	X12117	222	224	0.78	0.19	31	2.9	0.1	36	20	65	AS7-5679a
M-07-53	X12118	224	226	1.13	0.20	29	2.6	0.1	68	25	102	AS7-5679a
M-07-53	X12119	226	227	0.83	0.18	24	3.1	0.1	44	10	84	AS7-5679a
M-07-53	X12120	227	228	0.45	0.13	17	2.2	5	42	15	125	AS7-5679a
M-07-53	X12121	228	230	0.85	0.43	22	10.3	0.1	100	25	110	AS7-5679a
M-07-53	X12122	230	232	0.68	0.21	26	3.3	0.1	38	25	89	AS7-5679a
M-07-53	X12123	232	234	0.97	0.16	27	2.7	15	48	25	90	AS7-5679a
M-07-53	X12124	234	236	1.15	0.51	23	6.8	0.1	38	15	66	AS7-5679a
M-07-53	X12125	236	238	0.63	0.16	21	2.6	10	68	10	144	AS7-5679a
M-07-53	X12126	238	240	1.76	0.52	20	8	10	58	15	543	AS7-5679a
M-07-53	X12127	240	242	0.95	0.17	29	2.4	0.1	30	45	105	AS7-5679a
M-07-53	X12128	242	244	0.85	0.15	21	2.1	5	44	20	81	AS7-5679a
M-07-53	X12129	244	246	1.28	0.39	22	5	0.1	30	10	55	AS7-5679a
M-07-53	X12131	246	248	0.76	0.22	22	3.2	0.1	34	15	63	AS7-5679a
M-07-53	X12132	248	250	1.09	0.31	23	4.4	0.1	38	25	104	AS7-5679a
M-07-53	X12133	250	252	0.73	0.15	24	2.6	10	40	25	62	AS7-5679a
M-07-53	X12134	252	254	0.74	0.16	24	2.3	20	30	30	57	AS7-5679a
M-07-53	X12136	254	256	0.65	0.16	20	2.6	15	52	10	70	AS7-5679a
M-07-53	X12137	256	258	0.59	0.14	22	2.1	10	26	15	73	AS7-5679a
M-07-53	X12138	258	260	0.66	0.15	23	2.2	15	32	35	62	AS7-5679a
M-07-53	X12139	260	262	0.66	0.14	23	2.6	10	38	25	84	AS7-5679a
M-07-53	X12141	262	264	0.94	0.21	12	3.2	25	34	0.1	89	AS7-5675a
M-07-53	X12142	264	266	0.48	0.12	15	2	20	16	0.1	57	AS7-5675a
M-07-53	X12143	266	268	0.81	0.15	12	1.9	10	14	0.1	72	AS7-5675a
M-07-53	X12144	268	270	0.63	0.19	11	2.8	10	14	0.1	65	AS7-5675a
M-07-53	X12145	270	272	0.43	0.18	13	2.5	10	14	0.1	64	AS7-5675a
M-07-53	X12146	272	274	0.75	0.21	13	2.5	15	26	0.1	81	AS7-5675a
M-07-53	X12147	274	276	0.57	0.18	9	2.4	10	14	0.1	52	AS7-5675a
M-07-53	X12148	276	278	0.91	0.14	12	2.2	15	114	0.1	159	AS7-5675a
M-07-53	X12149	278	280	0.59	0.15	11	2.1	15	22	0.1	62	AS7-5675a
M-07-53	X12150	280	282	0.64	0.19	10	2.6	10	24	0.1	71	AS7-5675a
M-07-53	X12151	282	284	0.98	0.27	10	3.9	15	40	0.1	100	AS7-5675a
M-07-53	X12152	284	286	1.42	0.28	8	3.7	25	16	0.1	101	AS7-5675a
M-07-53	X12153	286	288	0.74	0.15	10	2.4	15	16	0.1	73	AS7-5675a
M-07-53	X12154	288	290	0.61	0.18	9	3.1	15	26	0.1	66	AS7-5675a
M-07-53	X12155	290	292	1.14	0.20	9	2.9	55	60	0.1	103	AS7-5675a
M-07-53	X12156	292	294	0.58	0.10	10	1.8	30	32	0.1	94	AS7-5675a
M-07-53	X12157	294	296	0.56	0.11	9	1.6	20	28	0.1	51	AS7-5675a
M-07-53	X12158	296	298	0.57	0.12	10	1.9	20	18	0.1	91	AS7-5675a
M-07-53	X12159	298	300	0.48	0.13	13	1.8	15	16	0.1	75	AS7-5675a
M-07-53	X12160	300	302	0.54	0.13	12	1.7	15	18	0.1	53	AS7-5675a
M-07-53	X12161	302	304	0.51	0.13	11	1.9	15	14	0.1	70	AS7-5675a
M-07-53	X12162	304	306	0.49	0.09	11	1.3	10	14	0.1	44	AS7-5675a
M-07-53	X12163	306	308	0.76	0.10	10	1.4	10	16	0.1	62	AS7-5675a
M-07-53	X12164	308	310	0.63	0.15	12	2.1	15	16	0.1	63	AS7-5675a
M-07-53	X12165	310	312	0.67	0.15	9	2.2	15	26	0.1	65	AS7-5675a
M-07-53	X12166	312	314	0.61	0.16	8	1.9	15	18	0.1	72	AS7-5675a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-53	X12167	314	316	0.80	0.17	10	2.6	20	30	0.1	125	AS7-5675a
M-07-53	X12168	316	318	0.59	0.18	9	2.4	20	26	0.1	68	AS7-5675a
M-07-53	X12169	318	320	0.97	0.19	9	2.4	20	22	0.1	78	AS7-5675a
M-07-53	X12170	320	322	0.70	0.19	9	2.5	15	24	0.1	67	AS7-5675a
M-07-53	X12171	322	324	0.61	0.21	8	2.6	15	20	0.1	128	AS7-5675a
M-07-53	X12173	324	326	0.86	0.16	8	3.1	20	28	0.1	101	AS7-5675a
M-07-53	X12176	326	328.25	0.66	0.15	18	2.3	0.1	52	0.1	88	AS7-5692a
M-07-53	X12177	328.25	330	0.53	0.17	13	2.3	0.1	32	0.1	111	AS7-5692a
M-07-53	X12178	330	332	0.85	0.22	16	3.5	0.1	54	5	89	AS7-5692a
M-07-53	X12179	332	334	0.58	0.13	17	1.5	0.1	30	0.1	65	AS7-5692a
M-07-53	X12180	334	336	0.64	0.14	20	1.9	0.1	70	0.1	100	AS7-5692a
M-07-53	X12181	336	338	1.28	0.11	16	2.5	60	30	5	55	AS7-5692a
M-07-53	X12182	338	340	0.46	0.12	19	1.3	0.1	26	0.1	52	AS7-5692a
M-07-53	X12183	340	342	0.50	0.11	21	1.5	0.1	38	25	67	AS7-5692a
M-07-53	X12184	342	344	0.72	0.20	18	2.4	0.1	42	0.1	88	AS7-5692a
M-07-53	X12185	344	346	0.66	0.12	14	1.3	0.1	32	0.1	61	AS7-5692a
M-07-53	X12186	346	348	0.76	0.22	15	2.5	0.1	34	0.1	57	AS7-5692a
M-07-53	X12187	348	350	0.85	0.24	14	3.1	0.1	30	0.1	66	AS7-5692a
M-07-53	X12188	350	352	0.62	0.13	17	1.6	0.1	40	0.1	125	AS7-5692a
M-07-53	X12189	352	354	0.80	0.27	14	3.4	0.1	32	0.1	72	AS7-5692a
M-07-53	X12190	354	356	0.83	0.14	15	1.5	0.1	34	0.1	56	AS7-5692a
M-07-53	X12191	356	358	0.57	0.11	12	1.3	0.1	20	0.1	46	AS7-5692a
M-07-53	X12192	358	360	0.65	0.18	21	2	0.1	42	0.1	104	AS7-5692a
M-07-53	X12193	360	362	0.61	0.14	16	1.9	0.1	50	0.1	102	AS7-5692a
M-07-53	X12194	362	364	0.71	0.15	12	1.6	10	38	0.1	72	AS7-5692a
M-07-53	X12195	364	366	0.85	0.18	13	2.5	0.1	40	0.1	56	AS7-5692a
M-07-53	X12196	366	368	0.49	0.10	16	1.4	0.1	28	0.1	69	AS7-5692a
M-07-53	X12197	368	370	1.12	0.29	14	3.2	0.1	48	0.1	91	AS7-5692a
M-07-53	X12198	370	372	0.91	0.16	14	3.4	10	46	0.1	89	AS7-5692a
M-07-53	X12199	372	374	0.58	0.14	15	1.6	0.1	30	0.1	73	AS7-5692a
M-07-53	X12201	374	376	0.47	0.08	14	1	0.1	34	0.1	79	AS7-5692a
M-07-53	X12202	376	378	0.74	0.18	13	1.8	0.1	40	0.1	76	AS7-5692a
M-07-53	X12203	378	380	0.65	0.15	17	1.7	0.1	38	0.1	59	AS7-5692a
M-07-53	X12204	380	382	0.44	0.07	20	1.1	0.1	30	15	65	AS7-5692a
M-07-53	X12205	382	384	0.52	0.07	15	1.4	15	42	15	100	AS7-5692a
M-07-53	X12206	384	386	0.46	0.08	16	1.3	15	34	10	79	AS7-5692a
M-07-53	X12207	386	388	0.71	0.17	17	2.7	5	42	5	97	AS7-5692a
M-07-53	X12208	388	390	0.61	0.15	12	2.5	10	48	0.1	64	AS7-5692a
M-07-53	X12211	390	392	0.90	0.11	12	2.4	50	18	0.1	77	AS7-5704a
M-07-53	X12212	392	394	0.89	0.09	11	2.4	100	16	5	58	AS7-5704a
M-07-53	X12213	394	396	0.71	0.12	11	1.9	25	12	0.1	61	AS7-5704a
M-07-53	X12214	396	398	0.96	0.19	10	2.9	35	14	0.1	59	AS7-5704a
M-07-53	X12215	398	400	0.63	0.19	14	2.8	20	16	0.1	69	AS7-5704a
M-07-53	X12216	400	402	0.54	0.15	10	2.1	20	16	0.1	87	AS7-5704a
M-07-53	X12217	402	404	1.22	0.32	17	4.2	25	22	0.1	60	AS7-5704a
M-07-53	X12218	404	406	0.95	0.18	8	2.4	45	18	0.1	80	AS7-5704a
M-07-53	X12219	406	408	0.61	0.15	11	2.1	25	24	0.1	96	AS7-5704a
M-07-53	X12220	408	410	0.76	0.14	8	3.2	50	16	0.1	77	AS7-5704a
M-07-53	X12221	410	412	0.81	0.14	11	6	80	14	0.1	65	AS7-5704a
M-07-53	X12222	412	414	0.60	0.11	11	2.9	60	16	0.1	79	AS7-5704a
M-07-53	X12223	414	416	0.75	0.08	11	3	110	20	5	63	AS7-5704a
M-07-53	X12224	416	417.6	1.86	0.09	22	5.9	90	20	10	44	AS7-5704a
M-07-53	X12225	417.6	420.3	1.19	0.08	8	3.3	85	18	10	31	AS7-5704a
M-07-53	X12227	420.3	422	1.06	0.11	10	2.4	80	14	0.1	62	AS7-5704a
M-07-53	X12228	422	424	0.48	0.08	9	1.5	70	10	0.1	96	AS7-5704a
M-07-53	X12229	424	426	0.70	0.10	11	2	40	10	0.1	92	AS7-5704a
M-07-53	X12230	426	428	0.62	0.09	8	1.8	125	14	0.1	62	AS7-5704a
M-07-53	X12231	428	430	0.61	0.08	13	1.8	80	16	0.1	45	AS7-5704a
M-07-53	X12232	430	432	0.58	0.13	5	2.3	35	14	0.1	55	AS7-5704a
M-07-53	X12233	432	434	0.51	0.06	9	1.5	55	12	0.1	77	AS7-5704a
M-07-53	X12234	434	436	0.32	0.10	6	1.6	60	10	0.1	75	AS7-5704a
M-07-53	X12235	436	438	0.54	0.10	7	1.6	50	10	0.1	77	AS7-5704a
M-07-53	X12236	438	440	0.48	0.12	7	1.9	55	12	0.1	78	AS7-5704a
M-07-53	X12237	440	442	0.30	0.08	9	1.4	45	10	0.1	53	AS7-5704a
M-07-53	X12238	442	444	0.33	0.06	8	1	25	8	0.1	50	AS7-5704a
M-07-53	X12239	444	446	1.56	0.06	7	1.3	35	16	0.1	66	AS7-5704a
M-07-53	X12240	446	448	0.34	0.11	5	1.5	10	14	0.1	48	AS7-5704a
M-07-53	X12242	448	450	0.37	0.08	8	1.2	30	12	0.1	70	AS7-5704a
M-07-53	X12243	450	452	0.54	0.11	8	1.6	50	14	0.1	107	AS7-5704a
M-07-53	X12244	452	454	0.40	0.14	8	1.8	15	12	0.1	64	AS7-5704a
M-07-53	X12245	454	456	0.26	0.08	8	1	10	22	0.1	81	AS7-5704a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-53	X12246	456	458	0.34	0.09	16	0.9	0.1	24	5	98	AS7-5698a
M-07-53	X12247	458	460	0.19	0.05	13	0.6	0.1	28	0.1	110	AS7-5698a
M-07-53	X12248	460	462	0.43	0.06	14	1.1	0.1	28	10	114	AS7-5698a
M-07-53	X12249	462	464	0.15	0.04	17	0.3	0.1	34	20	123	AS7-5698a
M-07-53	X12250	464	466	0.34	0.10	11	1	0.1	28	0.1	119	AS7-5698a
M-07-53	X12251	466	468	0.68	0.15	14	1.9	0.1	24	0.1	91	AS7-5698a
M-07-53	X12252	468	470	0.37	0.13	13	1.7	0.1	32	10	101	AS7-5698a
M-07-53	X12253	470	472	0.35	0.07	15	1	0.1	24	15	135	AS7-5698a
M-07-53	X12254	472	474	0.32	0.15	9	2.1	0.1	24	5	124	AS7-5698a
M-07-53	X12255	474	476	0.31	0.07	12	0.8	0.1	22	10	110	AS7-5698a
M-07-53	X12256	476	478	0.39	0.09	13	1.3	5	26	10	106	AS7-5698a
M-07-53	X12257	478	480	0.64	0.09	15	1.4	10	30	15	91	AS7-5698a
M-07-53	X12258	480	482	0.27	0.07	11	1	0.1	26	5	95	AS7-5698a
M-07-53	X12259	482	484	0.46	0.07	17	1.6	30	52	25	319	AS7-5698a
M-07-53	X12260	484	486	0.33	0.08	9	1.3	0.1	28	0.1	75	AS7-5698a
M-07-53	X12261	486	488	0.51	0.11	14	2.3	15	32	15	82	AS7-5698a
M-07-53	X12262	488	490	0.32	0.10	14	2.3	0.1	32	20	63	AS7-5698a
M-07-53	X12263	490	492	0.50	0.12	16	2.6	0.1	32	10	146	AS7-5698a
M-07-53	X12264	492	494	0.34	0.13	12	2.1	0.1	24	10	128	AS7-5698a
M-07-53	X12266	494	496	0.54	0.12	13	2.2	0.1	34	10	138	AS7-5698a
M-07-53	X12267	496	498	0.47	0.12	14	1.9	0.1	30	20	104	AS7-5698a
M-07-53	X12268	498	500	-1.00								
M-07-53	X12269	500	502	0.74	0.21	15	2.7	0.1	30	10	118	AS7-5698a
M-07-53	X12270	502	504	0.36	0.10	15	1.3	0.1	36	15	103	AS7-5698a
M-07-53	X12271	504	506	0.54	0.13	10	1.6	0.1	24	0.1	69	AS7-5698a
M-07-53	X12272	506	508	0.34	0.08	13	1	0.1	28	10	153	AS7-5698a
M-07-53	X12273	508	510	0.38	0.09	15	2	0.1	26	10	88	AS7-5698a
M-07-53	X12274	510	512	3.90	0.13	11	12.2	5	30	15	87	AS7-5698a
M-07-53	X12275	512	514	0.25	0.08	14	1.2	0.1	26	10	84	AS7-5698a
M-07-53	X12276	514	516	0.48	0.12	13	1.3	0.1	28	5	85	AS7-5698a
M-07-53	X12277	516	518	0.24	0.09	12	0.9	0.1	24	5	82	AS7-5698a
M-07-53	X12278	518	520	0.36	0.08	14	0.8	0.1	48	10	104	AS7-5698a
M-07-53	X12281	520	522	0.34	0.08	13	0.9	0.1	46	10	91	AS7-5697a
M-07-53	X12282	522	524	0.42	0.14	10	1.6	0.1	48	0.1	80	AS7-5697a
M-07-53	X12283	524	526	0.65	0.21	13	3.2	10	40	10	98	AS7-5697a
M-07-53	X12284	526	528	0.27	0.11	12	2.3	5	48	0.1	181	AS7-5697a
M-07-53	X12285	528	530	0.29	0.13	14	4.8	5	88	10	112	AS7-5697a
M-07-53	X12286	530	532	0.31	0.08	11	1.6	0.1	40	0.1	107	AS7-5697a
M-07-53	X12287	532	534	0.29	0.09	14	1.8	0.1	42	5	88	AS7-5697a
M-07-53	X12288	534	536	0.72	0.27	12	3.1	0.1	32	0.1	54	AS7-5697a
M-07-53	X12289	536	538	0.21	0.07	14	1.1	0.1	36	10	67	AS7-5697a
M-07-53	X12290	538	540	0.22	0.08	14	1.7	0.1	56	0.1	37	AS7-5697a
M-07-53	X12291	540	542	0.26	0.07	16	1.2	0.1	34	15	63	AS7-5697a
M-07-53	X12292	542	544	0.31	0.08	12	1.7	10	30	5	59	AS7-5697a
M-07-53	X12293	544	546	0.54	0.08	15	7.2	50	274	5	1155	AS7-5697a
M-07-53	X12294	546	548	0.40	0.14	15	5.8	85	144	25	447	AS7-5697a
M-07-53	X12295	548	550	0.23	0.06	13	2.3	15	52	15	129	AS7-5697a
M-07-53	X12296	550	552	0.19	0.05	13	1.2	15	40	15	75	AS7-5697a
M-07-53	X12297	552	554	0.16	0.05	15	1	10	48	25	78	AS7-5697a
M-07-53	X12298	554	556	0.42	0.10	15	2	20	38	15	56	AS7-5697a
M-07-53	X12299	556	558	0.47	0.12	11	2.3	5	36	0.1	53	AS7-5697a
M-07-53	X12300	558	560	0.35	0.07	15	1.3	0.1	42	10	80	AS7-5697a
M-07-53	X12301	560	562	0.32	0.08	13	1.9	0.1	30	10	60	AS7-5697a
M-07-53	X12302	562	564	0.29	0.08	17	2.3	10	34	35	83	AS7-5697a
M-07-53	X12303	564	566	0.21	0.06	16	3.4	15	66	10	220	AS7-5697a
M-07-53	X12304	566	568	0.33	0.08	12	9.8	45	36	15	55	AS7-5697a
M-07-53	X12305	568	570.5	0.49	0.06	9	19.5	85	74	10	71	AS7-5697a
M-07-53	X12306	570.5	572.75	0.04	0.00	10	0.2	35	58	30	105	AS7-5697a
M-07-53	X12307	572.75	574	0.48	0.12	14	3.9	40	50	15	65	AS7-5697a
M-07-53	X12308	574	576	0.43	0.19	12	2.3	0.1	30	10	33	AS7-5697a
M-07-53	X12309	576	578	0.40	0.21	9	2.4	0.1	20	10	28	AS7-5697a
M-07-53	X12310	578	580	0.32	0.15	11	1.3	0.1	28	0.1	44	AS7-5697a
M-07-53	X12311	580	582	0.23	0.14	11	1.4	0.1	30	5	38	AS7-5697a
M-07-53	X12313	582	584	0.27	0.09	13	1	0.1	28	20	32	AS7-5697a
M-07-53	X12314	584	586	0.33	0.09	13	1.1	0.1	30	20	31	AS7-5697a
M-07-53	X12316	586	588	0.40	0.15	9	1.6	0.1	32	5	33	AS7-5693a
M-07-53	X12317	588	590	0.69	0.17	10	1.9	0.1	26	5	34	AS7-5693a
M-07-53	X12318	590	592	0.27	0.12	11	1.3	0.1	26	0.1	34	AS7-5693a
M-07-53	X12319	592	594	0.39	0.17	12	1.4	0.1	28	15	38	AS7-5693a
M-07-53	X12320	594	596	0.38	0.14	10	1.2	0.1	26	0.1	39	AS7-5693a
M-07-53	X12321	596	598	0.30	0.12	11	1.4	0.1	28	10	45	AS7-5693a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-53	X12322	598	600	0.26	0.08	10	1	0.1	30	10	45	AS7-5693a
M-07-53	X12323	600	602	0.32	0.09	10	1.2	0.1	30	10	40	AS7-5693a
M-07-53	X12324	602	604	0.18	0.07	8	0.9	0.1	24	0.1	44	AS7-5693a
M-07-53	X12325	604	606	0.36	0.22	9	2.4	0.1	24	0.1	42	AS7-5693a
M-07-53	X12326	606	608	0.20	0.10	11	1.1	0.1	22	0.1	41	AS7-5693a
M-07-53	X12327	608	610	0.49	0.07	11	0.7	0.1	26	10	56	AS7-5693a
M-07-53	X12328	610	612	0.64	0.10	8	1.5	0.1	26	0.1	57	AS7-5693a
M-07-53	X12329	612	614	0.28	0.12	10	1.7	0.1	24	0.1	39	AS7-5693a
M-07-53	X12330	614	616	0.17	0.09	13	1	0.1	30	15	52	AS7-5693a
M-07-53	X12331	616	618	0.19	0.08	10	0.8	0.1	22	0.1	55	AS7-5693a
M-07-53	X12332	618	620	0.18	0.11	12	1.7	0.1	26	5	48	AS7-5693a
M-07-53	X12333	620	622	0.37	0.16	10	1.7	0.1	24	0.1	69	AS7-5693a
M-07-53	X12334	622	624	0.31	0.10	12	1.2	0.1	24	0.1	75	AS7-5693a
M-07-53	X12335	624	626	0.23	0.15	11	1.4	0.1	34	0.1	74	AS7-5693a
M-07-53	X12336	626	628	0.21	0.13	9	1.1	0.1	24	0.1	63	AS7-5693a
M-07-53	X12337	628	630	0.21	0.08	10	1.2	0.1	26	0.1	39	AS7-5693a
M-07-53	X12338	630	632	0.43	0.21	17	2.3	0.1	28	0.1	35	AS7-5693a
M-07-53	X12339	632	634	0.37	0.12	11	1.7	0.1	30	5	47	AS7-5693a
M-07-53	X12340	634	636	0.18	0.08	9	1.5	0.1	28	5	49	AS7-5693a
M-07-53	X12341	636	638	0.38	0.15	12	2.1	0.1	28	20	54	AS7-5693a
M-07-53	X12342	638	640	0.22	0.08	11	1.1	0.1	34	10	58	AS7-5693a
M-07-53	X12343	640	642	0.25	0.11	13	1.2	0.1	32	10	52	AS7-5693a
M-07-53	X12344	642	644	0.49	0.18	14	1.7	0.1	26	10	56	AS7-5693a
M-07-53	X12345	644	646	0.46	0.18	13	2.3	10	30	15	47	AS7-5693a
M-07-53	X12348	646	648	0.40	0.17	10	1.9	0.1	30	0.1	53	AS7-5693a
M-07-53	X12349	648	650	0.47	0.15	11	2	0.1	32	10	65	AS7-5693a
M-07-53	X12350	650	652	0.28	0.10	13	1.4	0.1	36	5	68	AS7-5693a
M-07-53	X12351	652	654	0.25	0.13	13	1.6	0.1	16	10	30	AS7-5729a
M-07-53	X12352	654	656	0.22	0.09	10	1.5	0.1	22	15	38	AS7-5729a
M-07-53	X12353	656	658	0.25	0.10	10	5.8	30	52	5	49	AS7-5729a
M-07-53	X12354	658	660	0.32	0.09	11	5.3	5	38	15	59	AS7-5729a
M-07-53	X12355	660	662	0.35	0.10	7	1.5	15	22	0.1	50	AS7-5729a
M-07-53	X12356	662	664	0.14	0.08	11	1.1	0.1	24	25	55	AS7-5729a
M-07-53	X12357	664	666	0.28	0.17	14	2	0.1	24	15	64	AS7-5729a
M-07-53	X12358	666	668	0.27	0.13	10	1.8	10	20	15	41	AS7-5729a
M-07-53	X12359	668	670	0.38	0.19	13	2.1	0.1	24	20	62	AS7-5729a
M-07-53	X12360	670	672	0.22	0.11	14	1.1	0.1	18	0.1	56	AS7-5729a
M-07-53	X12361	672	674.79	0.59	0.27	17	2.9	0.1	30	45	87	AS7-5729a
M-07-54	X10079	3.5	5	0.49	0.12	30	1.7	0.1	30	15	91	AS7-5680a
M-07-54	X10080	5	7	0.76	0.24	20	3.1	0.1	40	15	98	AS7-5680a
M-07-54	X10081	7	9	0.50	0.12	19	1.5	0.1	40	10	147	AS7-5680a
M-07-54	X10082	9	11	0.44	0.11	27	1.3	0.1	34	20	105	AS7-5680a
M-07-54	X10083	11	13	0.60	0.20	25	2.3	5	36	10	92	AS7-5680a
M-07-54	X10084	13	15	0.50	0.19	24	2.8	25	36	20	187	AS7-5680a
M-07-54	X10085	15	17	0.35	0.13	15	1.6	0.1	44	0.1	84	AS7-5680a
M-07-54	X10086	17	19	0.57	0.14	17	1.8	0.1	26	10	75	AS7-5680a
M-07-54	X10087	19	21	0.58	0.11	25	1.9	5	142	15	124	AS7-5680a
M-07-54	X10088	21	23	0.67	0.13	26	1.6	0.1	22	5	63	AS7-5680a
M-07-54	X10089	23	25	0.54	0.17	21	2.2	0.1	94	10	92	AS7-5680a
M-07-54	X10090	25	27	0.40	0.12	21	1.5	0.1	22	0.1	51	AS7-5680a
M-07-54	X10091	27	29	0.64	0.17	19	2	0.1	26	0.1	34	AS7-5680a
M-07-54	X10092	29	31	1.14	0.35	30	3.7	5	36	0.1	32	AS7-5680a
M-07-54	X10093	31	33	0.75	0.17	17	1.8	0.1	26	10	52	AS7-5680a
M-07-54	X10094	33	35	0.53	0.13	15	1.7	0.1	16	10	28	AS7-5680a
M-07-54	X10095	35	37	0.88	0.26	14	3.9	0.1	40	10	45	AS7-5680a
M-07-54	X10096	37	39	0.59	0.12	18	1.4	0.1	30	10	70	AS7-5680a
M-07-54	X10097	39	41	0.48	0.14	23	1.6	0.1	36	15	71	AS7-5680a
M-07-54	X10098	41	43	0.70	0.17	21	2.3	0.1	52	25	70	AS7-5680a
M-07-54	X10099	43	45	0.90	0.28	19	3.6	0.1	72	10	65	AS7-5680a
M-07-54	X10100	45	47	1.19	0.28	16	3.6	10	78	10	71	AS7-5680a
M-07-54	X10101	47	49	0.71	0.19	17	2.1	5	22	15	90	AS7-5680a
M-07-54	X10102	49	51	0.72	0.16	16	1.7	0.1	30	15	90	AS7-5680a
M-07-54	X10105	51	53	0.65	0.18	22	1.9	5	28	10	129	AS7-5680a
M-07-54	X10106	53	55.4	0.46	0.22	18	2.2	0.1	32	10	86	AS7-5680a
M-07-54	X10107	55.4	57	0.40	0.55	11	8.4	20	54	20	75	AS7-5680a
M-07-54	X10108	57	58.75	2.25	0.60	14	34.5	140	126	145	369	AS7-5680a
M-07-54	X10109	58.75	61	0.88	0.34	17	5.9	0.1	76	20	80	AS7-5680a
M-07-54	X10110	61	63	0.66	0.19	15	2.2	0.1	40	10	81	AS7-5680a
M-07-54	X10111	63	65	0.63	0.23	24	2.4	0.1	50	10	77	AS7-5680a
M-07-54	X10112	65	67	1.19	0.39	15	3.4	0.1	30	20	95	AS7-5683a
M-07-54	X10113	67	69	1.08	0.47	15	4.6	0.1	60	25	80	AS7-5683a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-54	X10114	69	71	0.99	0.43	19	3.7	0.1	30	20	89	AS7-5683a
M-07-54	X10115	71	73	0.59	0.19	27	2.1	0.1	30	20	167	AS7-5683a
M-07-54	X10116	73	75	0.58	0.20	26	2.3	0.1	36	25	166	AS7-5683a
M-07-54	X10117	75	77	0.52	0.19	29	2.3	0.1	40	20	144	AS7-5683a
M-07-54	X10118	77	79	0.88	0.30	25	3	0.1	46	25	136	AS7-5683a
M-07-54	X10119	79	80.6	0.69	0.24	23	2.1	0.1	42	15	107	AS7-5683a
M-07-54	X10120	80.6	82	0.48	0.37	21	3.8	5	56	10	93	AS7-5683a
M-07-54	X10121	82	84	0.56	0.19	25	4.1	0.1	62	30	127	AS7-5683a
M-07-54	X10123	84	86	0.50	0.21	29	3.8	0.1	28	10	68	AS7-5683a
M-07-54	X10124	86	88	0.41	0.23	19	8.1	10	120	30	454	AS7-5683a
M-07-54	X10125	88	90	0.45	0.24	25	4.7	35	38	20	148	AS7-5683a
M-07-54	X10126	90	92	0.54	0.32	25	33.2	80	624	160	1528	AS7-5683a
M-07-54	X10128	92	94	0.71	0.29	28	21.7	40	336	80	865	AS7-5683a
M-07-54	X10129	94	96	0.73	0.24	23	3.5	0.1	44	0.1	77	AS7-5683a
M-07-54	X10130	96	98.2	0.73	0.26	25	2.8	0.1	80	10	58	AS7-5683a
M-07-54	X10131	98.2	100	0.56	0.19	29	2.3	0.1	228	15	278	AS7-5683a
M-07-54	X10132	100	102	1.57	0.33	28	3.8	0.1	56	25	95	AS7-5683a
M-07-54	X10133	102	104	0.70	0.18	21	2.1	0.1	62	40	89	AS7-5683a
M-07-54	X10134	104	106	0.75	0.22	17	2.3	0.1	44	30	90	AS7-5683a
M-07-54	X10135	106	108	0.55	0.20	21	2.1	5	40	25	55	AS7-5683a
M-07-54	X10136	108	110	0.45	0.26	12	3.4	0.1	50	15	69	AS7-5683a
M-07-54	X10137	110	111.2	0.49	0.18	21	2.4	0.1	32	15	70	AS7-5683a
M-07-54	X10138	111.2	113	0.54	0.35	12	14.1	25	102	20	149	AS7-5683a
M-07-54	X10139	113	115	0.57	0.28	15	87	85	368	95	316	AS7-5683a
M-07-54	X10140	115	117	0.66	0.28	17	33.2	205	236	170	271	AS7-5683a
M-07-54	X10141	117	119	1.02	0.32	16	11.4	30	72	25	122	AS7-5683a
M-07-54	X10142	119	120	0.69	0.42	10	19.2	75	70	45	132	AS7-5683a
M-07-54	X10143	120	122	0.69	0.27	17	5.7	15	48	20	89	AS7-5683a
M-07-54	X10144	122	124	0.93	0.26	24	4	0.1	48	40	77	AS7-5683a
M-07-54	X10146	124	126	1.30	0.35	20	4.3	0.1	40	0.1	65	AS7-5683a
M-07-54	X10147	126	128	1.00	0.24	28	4.8	20	120	10	282	AS7-5681a
M-07-54	X10148	128	130	1.99	0.46	16	32.5	100	30	160	125	AS7-5681a
M-07-54	X10150	130	132	1.57	0.40	19	6.4	15	58	15	37	AS7-5681a
M-07-54	X10151	132	134	4.96	0.40	26	5.8	25	34	20	44	AS7-5681a
M-07-54	X10153	134	136	1.64	0.38	18	4.4	10	82	20	195	AS7-5681a
M-07-54	X10154	136	138	2.23	0.34	22	3.8	10	192	20	270	AS7-5681a
M-07-54	X10155	138	140	2.07	0.42	17	4.9	10	68	15	100	AS7-5681a
M-07-54	X10156	140	142	1.44	0.41	16	5.4	20	58	10	90	AS7-5681a
M-07-54	X10157	142	144	1.30	0.36	17	3.8	20	36	15	68	AS7-5681a
M-07-54	X10158	144	146	1.05	0.30	19	3.7	15	60	15	87	AS7-5681a
M-07-54	X10159	146	148	1.19	0.28	20	3.8	15	66	25	130	AS7-5681a
M-07-54	X10160	148	150	1.40	0.32	17	4.2	20	68	15	67	AS7-5681a
M-07-54	X10161	150	152	1.12	0.29	24	4	0.1	62	0.1	33	AS7-5681a
M-07-54	X10162	152	154	1.24	0.34	14	4.4	10	60	10	91	AS7-5681a
M-07-54	X10163	154	156	1.31	0.37	14	4.7	0.1	84	20	196	AS7-5681a
M-07-54	X10164	156	158	1.74	0.50	38	6.1	15	214	15	716	AS7-5681a
M-07-54	X10165	158	160	1.52	0.30	18	3.7	0.1	44	15	105	AS7-5681a
M-07-54	X10166	160	162	1.37	0.26	18	3.1	15	42	25	80	AS7-5681a
M-07-54	X10167	162	164	1.23	0.29	17	4.2	10	162	20	357	AS7-5681a
M-07-54	X10168	164	166	1.41	0.45	14	4.6	5	40	0.1	39	AS7-5681a
M-07-54	X10169	166	168	1.23	0.28	14	2.9	10	62	20	84	AS7-5681a
M-07-54	X10170	168	170	1.04	0.36	20	5.9	0.1	754	20	934	AS7-5681a
M-07-54	X10171	170	172	1.39	0.25	12	3.6	15	88	0.1	129	AS7-5681a
M-07-54	X10172	172	174	1.16	0.25	20	3.8	10	130	25	273	AS7-5681a
M-07-54	X10173	174	176	2.68	0.37	21	3.6	10	36	15	73	AS7-5681a
M-07-54	X10174	176	178	1.83	0.35	15	3.9	0.1	36	10	63	AS7-5681a
M-07-54	X10175	178	179.4	1.26	0.20	19	3.2	25	38	30	66	AS7-5681a
M-07-54	X10176	179.4	181	1.76	0.30	21	3.5	20	46	20	70	AS7-5681a
M-07-54	X10177	181	183	1.61	0.26	16	3.1	5	30	15	59	AS7-5681a
M-07-54	X10178	183	185	1.59	0.32	15	4	30	64	10	105	AS7-5681a
M-07-54	X10179	185	187	0.95	0.25	17	3	15	42	15	78	AS7-5681a
M-07-54	X10180	187	189	1.57	0.29	17	4	5	100	15	132	AS7-5681a
M-07-54	X10181	189	191	1.11	0.30	19	3.4	0.1	38	25	59	AS7-5681a
M-07-54	X10182	191	193	0.65	0.37	12	4.3	20	54	5	63	AS7-5684a
M-07-54	X10183	193	195	0.79	0.47	13	7.7	85	112	50	114	AS7-5684a
M-07-54	X10184	195	197	1.01	0.29	13	3.7	60	36	25	39	AS7-5684a
M-07-54	X10185	197	199	0.94	0.36	15	4.5	145	52	35	92	AS7-5684a
M-07-54	X10186	199	201	1.25	0.39	17	4.4	15	356	5	586	AS7-5684a
M-07-54	X10187	201	203	2.03	0.40	15	4.4	25	34	0.1	15	AS7-5684a
M-07-54	X10188	203	205	1.50	0.46	15	4.7	35	34	15	28	AS7-5684a
M-07-54	X10189	205	207	1.14	0.42	18	4.1	0.1	38	20	45	AS7-5684a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-54	X10190	207	209	1.31	0.33	20	3.9	5	30	30	50	AS7-5684a
M-07-54	X10191	209	210.5	0.79	0.27	18	3	0.1	26	10	43	AS7-5684a
M-07-54	X10192	210.5	211.9	0.96	0.28	17	3.5	5	36	20	50	AS7-5684a
M-07-54	X10193	211.9	214	0.89	0.26	14	4.8	80	44	30	45	AS7-5684a
M-07-54	X10194	214	216	1.34	0.32	34	6.1	25	80	15	217	AS7-5684a
M-07-54	X10195	216	218	0.34	0.31	37	6.3	0.1	94	20	141	AS7-5684a
M-07-54	X10196	218	220	0.37	0.21	16	5.6	20	40	40	47	AS7-5684a
M-07-54	X10197	220	222	0.27	0.24	36	7	35	34	50	32	AS7-5684a
M-07-54	X10199	222	224	0.45	0.33	14	4.4	0.1	60	0.1	42	AS7-5684a
M-07-54	X10200	224	225.8	0.44	0.29	24	3.8	0.1	62	55	49	AS7-5684a
M-07-54	X10201	225.8	228	0.72	0.25	17	3.6	0.1	58	0.1	94	AS7-5684a
M-07-54	X10202	228	230	1.49	0.22	20	3.4	0.1	26	20	87	AS7-5684a
M-07-54	X10204	230	232	0.66	0.26	20	3.4	0.1	72	15	81	AS7-5684a
M-07-54	X10205	232	234	0.75	0.26	27	3	20	72	80	81	AS7-5684a
M-07-54	X10207	234	236	0.49	0.19	25	2.7	0.1	78	30	53	AS7-5684a
M-07-54	X10208	236	238	1.28	0.25	19	3.2	0.1	34	15	61	AS7-5684a
M-07-54	X10209	238	239.6	0.83	0.19	20	2.5	0.1	48	25	101	AS7-5684a
M-07-54	X10210	239.6	241	0.40	0.28	16	3.4	0.1	66	5	55	AS7-5684a
M-07-54	X10211	241	243	0.27	0.53	26	9.3	60	104	80	213	AS7-5684a
M-07-54	X10212	243	245	0.23	0.38	41	11.5	65	78	140	155	AS7-5684a
M-07-54	X10213	245	247	0.28	0.30	28	6.1	55	178	80	277	AS7-5684a
M-07-54	X10214	247	249	0.39	0.36	29	8	90	106	85	360	AS7-5684a
M-07-54	X10215	249	251	0.38	0.43	19	8.3	20	128	45	137	AS7-5684a
M-07-54	X10216	251	253	0.44	0.22	24	4.3	0.1	116	30	158	AS7-5684a
M-07-54	X10217	253	255	0.67	0.41	27	4.4	0.1	54	15	58	AS7-5685a
M-07-54	X10218	255	257	0.50	0.31	24	4	0.1	142	0.1	215	AS7-5685a
M-07-54	X10219	257	259	1.30	0.21	35	3.2	0.1	68	10	103	AS7-5685a
M-07-54	X10220	259	261	0.41	0.15	23	3.1	0.1	50	20	39	AS7-5685a
M-07-54	X10221	261	263	0.31	0.23	19	4.3	0.1	332	10	563	AS7-5685a
M-07-54	X10222	263	265	0.39	0.30	27	4.1	0.1	164	0.1	282	AS7-5685a
M-07-54	X10223	265	267	0.65	0.22	19	3.4	0.1	180	10	288	AS7-5685a
M-07-54	X10224	267	269	1.16	0.16	26	2.7	0.1	70	5	75	AS7-5685a
M-07-54	X10225	269	271	0.74	0.21	21	4.8	0.1	102	10	47	AS7-5685a
M-07-54	X10226	271	273	1.10	0.22	23	2.9	0.1	32	15	65	AS7-5685a
M-07-54	X10227	273	275	0.66	0.24	23	3.7	0.1	56	30	46	AS7-5685a
M-07-54	X10228	275	276.8	0.40	0.22	20	3.6	0.1	64	10	87	AS7-5685a
M-07-54	X10229	276.8	278	0.88	0.26	21	5.3	0.1	68	10	120	AS7-5685a
M-07-54	X10230	278	280	1.02	0.26	26	4.3	0.1	46	10	163	AS7-5685a
M-07-54	X10231	280	282	0.87	0.22	15	3.4	0.1	30	0.1	60	AS7-5685a
M-07-54	X10232	282	284	1.02	0.22	24	3.3	0.1	32	10	57	AS7-5685a
M-07-54	X10233	284	286	0.94	0.29	28	4.2	0.1	32	10	44	AS7-5685a
M-07-54	X10234	286	288	1.31	0.26	36	10.1	0.1	50	20	48	AS7-5685a
M-07-54	X10235	288	290	1.01	0.21	27	2.9	0.1	78	20	99	AS7-5685a
M-07-54	X10236	290	292	1.69	0.27	30	3.4	0.1	30	15	51	AS7-5685a
M-07-54	X10238	292	294	1.24	0.26	23	3.4	0.1	28	10	38	AS7-5685a
M-07-54	X10239	294	296	0.68	0.23	25	2.8	0.1	28	5	73	AS7-5685a
M-07-54	X10240	296	298	0.70	0.28	27	3.1	0.1	34	25	54	AS7-5685a
M-07-54	X10241	298	300	0.75	0.25	26	2.8	0.1	18	15	31	AS7-5685a
M-07-54	X10243	300	302	0.60	0.17	25	2.5	0.1	22	20	40	AS7-5685a
M-07-54	X10244	302	304	0.54	0.26	42	3.3	0.1	20	0.1	26	AS7-5685a
M-07-54	X10245	304	306	1.37	0.11	23	2.2	0.1	30	15	78	AS7-5685a
M-07-54	X10246	306	308	0.70	0.27	25	3.5	0.1	26	15	45	AS7-5685a
M-07-54	X10247	308	310	1.07	0.23	25	3.9	0.1	62	10	29	AS7-5685a
M-07-54	X10248	310	312	0.59	0.37	24	4.4	0.1	56	0.1	178	AS7-5685a
M-07-54	X10249	312	314	0.71	0.27	30	3.1	0.1	18	25	35	AS7-5685a
M-07-54	X10250	314	316	1.01	0.21	26	3.4	0.1	20	5	41	AS7-5685a
M-07-54	X10251	316	318	0.55	0.26	25	4.3	0.1	108	15	589	AS7-5685a
M-07-54	X10252	318	320	0.35	0.31	84	6.2	0.1	88	10	423	AS7-5686a
M-07-54	X10253	320	322	0.47	0.43	50	4.4	0.1	30	0.1	20	AS7-5686a
M-07-54	X10254	322	324	0.57	0.72	60	5.8	0.1	54	0.1	86	AS7-5686a
M-07-54	X10255	324	325.4	0.56	0.32	53	3.9	0.1	54	10	95	AS7-5686a
M-07-54	X10256	325.4	326.7	0.57	0.27	41	3.9	0.1	52	5	43	AS7-5686a
M-07-54	X10257	326.7	328	1.56	0.26	26	3.7	0.1	40	5	55	AS7-5686a
M-07-54	X10258	328	330	0.61	0.24	61	4.1	0.1	32	25	41	AS7-5686a
M-07-54	X10259	330	332	0.88	0.32	60	3.1	0.1	38	5	16	AS7-5686a
M-07-54	X10260	332	334	1.04	0.22	14	2.3	0.1	20	0.1	39	AS7-5686a
M-07-54	X10261	334	336	1.07	0.15	36	2.5	15	34	15	225	AS7-5686a
M-07-54	X10262	336	338	0.98	0.36	40	4.1	0.1	78	0.1	110	AS7-5686a
M-07-54	X10263	338	340	1.63	0.35	28	6.5	0.1	46	20	29	AS7-5686a
M-07-54	X10264	340	342	0.53	0.16	29	2	0.1	30	5	8	AS7-5686a
M-07-54	X10265	342	344	0.79	0.22	30	2.3	0.1	30	10	45	AS7-5686a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-54	X10266	344	346	1.33	0.26	13	2.7	0.1	28	10	84	AS7-5686a
M-07-54	X10267	346	348	0.92	0.64	25	8.7	0.1	50	15	59	AS7-5686a
M-07-54	X10268	348	350	1.18	0.37	28	4.4	0.1	56	10	30	AS7-5686a
M-07-54	X10269	350	352	2.69	0.69	17	7	0.1	32	0.1	28	AS7-5686a
M-07-54	X10270	352	354	0.97	0.29	21	3.5	0.1	28	10	26	AS7-5686a
M-07-54	X10271	354	356	0.97	0.22	23	2.7	0.1	24	10	50	AS7-5686a
M-07-54	X10272	356	358	1.11	0.29	20	3.4	0.1	40	10	46	AS7-5686a
M-07-54	X10273	358	360	0.61	0.23	18	2.6	0.1	24	15	53	AS7-5686a
M-07-54	X10274	360	362	0.53	0.39	79	4	0.1	54	10	40	AS7-5686a
M-07-54	X10275	362	364	0.70	0.48	24	4.1	0.1	32	10	34	AS7-5686a
M-07-54	X10276	364	366	0.79	0.40	56	3.7	0.1	26	5	34	AS7-5686a
M-07-54	X10278	366	368	1.03	0.32	23	3.2	0.1	26	15	44	AS7-5686a
M-07-54	X10279	368	370	0.63	0.20	16	2.2	0.1	36	15	49	AS7-5686a
M-07-54	X10281	370	372	1.14	0.44	14	3.9	0.1	40	30	63	AS7-5686a
M-07-54	X10284	372	374	1.01	0.28	18	2.9	10	74	25	71	AS7-5686a
M-07-54	X10285	374	376	0.97	0.23	29	3.8	15	38	15	50	AS7-5686a
M-07-54	X10286	376	378	0.71	0.17	10	3.2	0.1	24	10	39	AS7-5686a
M-07-54	X10287	378	380	0.63	0.14	7	2.5	50	14	0.1	50	AS7-5706a
M-07-54	X10288	380	382	0.50	0.13	91	1.8	20	8	0.1	50	AS7-5706a
M-07-54	X10289	382	384	0.57	0.34	8	4.4	15	12	0.1	59	AS7-5706a
M-07-54	X10291	384	386	0.71	0.22	25	3.2	30	14	0.1	57	AS7-5706a
M-07-54	X10292	386	388	0.63	0.22	7	2.7	15	14	0.1	42	AS7-5706a
M-07-54	X10293	388	390	0.99	0.33	9	3.8	20	12	0.1	40	AS7-5706a
M-07-54	X10295	390	392	0.83	0.23	11	3.1	15	10	0.1	55	AS7-5706a
M-07-54	X10296	392	394	0.80	0.25	18	3.9	25	16	0.1	91	AS7-5706a
M-07-54	X10297	394	396	0.78	0.21	38	3.3	35	20	0.1	79	AS7-5706a
M-07-54	X10298	396	398	0.73	0.18	9	2.6	25	18	0.1	101	AS7-5706a
M-07-54	X10299	398	400	1.40	0.27	9	3.3	25	18	0.1	120	AS7-5706a
M-07-54	X10300	400	402	1.00	0.32	8	4.1	15	16	0.1	70	AS7-5706a
M-07-54	X10301	402	404	0.74	0.26	30	5.3	20	12	0.1	85	AS7-5706a
M-07-54	X10302	404	406	0.61	0.17	7	7.7	35	18	0.1	109	AS7-5706a
M-07-54	X10303	406	408	0.57	0.18	13	9.7	50	18	10	91	AS7-5706a
M-07-54	X10304	408	410	0.86	0.29	10	3.7	20	16	0.1	61	AS7-5706a
M-07-54	X10305	410	412	0.64	0.18	14	3	30	54	5	161	AS7-5706a
M-07-54	X10306	412	414	4.95	0.23	8	13.9	85	28	5	83	AS7-5706a
M-07-54	X10307	414	416	0.83	0.22	10	3.9	30	12	0.1	109	AS7-5706a
M-07-54	X10308	416	418	0.62	0.22	9	2.6	15	28	0.1	70	AS7-5706a
M-07-54	X10309	418	420	1.06	0.20	12	5.1	50	18	0.1	81	AS7-5706a
M-07-54	X10310	420	422	1.01	0.16	9	2.8	40	24	0.1	319	AS7-5706a
M-07-54	X10311	422	424	0.82	0.29	11	3.5	15	22	0.1	120	AS7-5706a
M-07-54	X10312	424	426	0.47	0.14	7	1.9	15	16	0.1	101	AS7-5706a
M-07-54	X10313	426	428	0.36	0.09	11	1.1	15	14	0.1	44	AS7-5706a
M-07-54	X10314	428	430	0.72	0.22	7	2.4	15	38	0.1	127	AS7-5706a
M-07-54	X10315	430	432	0.68	0.27	14	6.8	15	24	0.1	138	AS7-5706a
M-07-54	X10316	432	434	0.77	0.29	8	4.3	15	54	0.1	154	AS7-5706a
M-07-54	X10317	434	436	0.83	0.38	9	3.4	10	22	0.1	54	AS7-5706a
M-07-54	X10318	436	438	0.77	0.24	10	2.9	15	30	0.1	115	AS7-5706a
M-07-54	X10319	438	440	0.53	0.06	10	1.5	15	30	0.1	200	AS7-5706a
M-07-54	X10320	440	442	0.61	0.24	13	6.5	50	36	5	61	AS7-5706a
M-07-54	X10321	442	444	0.56	0.15	10	2.1	10	12	0.1	88	AS7-5706a
M-07-54	X10322	444	446	0.56	0.15	6	1.6	10	16	0.1	65	AS7-5695a
M-07-54	X10323	446	448	0.11	0.04	6	0.6	10	16	0.1	68	AS7-5695a
M-07-54	X10324	448	450	0.29	0.06	8	0.9	10	22	0.1	97	AS7-5695a
M-07-54	X10325	450	452	0.29	0.13	8	2.8	15	10	0.1	85	AS7-5695a
M-07-54	X10326	452	454	0.67	0.12	6	22.2	25	32	5	24	AS7-5695a
M-07-54	X10327	454	456	0.64	0.11	13	2.7	30	12	0.1	52	AS7-5695a
M-07-54	X10328	456	458	0.40	0.07	38	0.9	10	8	0.1	47	AS7-5695a
M-07-54	X10329	458	460	0.34	0.12	32	1.6	25	22	0.1	64	AS7-5695a
M-07-54	X10330	460	462	0.44	0.27	6	2.9	15	24	0.1	46	AS7-5695a
M-07-54	X10331	462	464	0.26	0.19	8	2.5	5	30	0.1	13	AS7-5695a
M-07-54	X10332	464	466	0.63	0.29	41	3.5	15	20	0.1	44	AS7-5695a
M-07-54	X10333	466	468	0.47	0.12	6	3.4	25	16	0.1	51	AS7-5695a
M-07-54	X10334	468	470	0.23	0.10	14	4.7	15	40	0.1	32	AS7-5695a
M-07-54	X10335	470	472	0.48	0.09	9	3.2	20	20	5	59	AS7-5695a
M-07-54	X10336	472	474	0.76	0.16	36	3	15	16	0.1	61	AS7-5695a
M-07-54	X10337	474	476	0.49	0.17	8	8.3	20	46	0.1	43	AS7-5695a
M-07-54	X10338	476	478	0.98	0.26	6	11.3	25	308	5	189	AS7-5695a
M-07-54	X10339	478	480	0.88	0.31	9	7.4	15	20	0.1	45	AS7-5695a
M-07-54	X10340	480	482	1.01	0.31	11	11.1	35	44	0.1	112	AS7-5695a
M-07-54	X10341	482	484	0.37	0.11	7	2	20	40	0.1	93	AS7-5695a
M-07-54	X10342	484	486	0.44	0.12	9	1.9	10	26	0.1	74	AS7-5695a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-54	X10343	486	488	0.33	0.28	9	4.8	10	32	0.1	45	AS7-5695a
M-07-54	X10345	488	490	0.66	0.13	15	1.9	10	34	0.1	63	AS7-5695a
M-07-54	X10346	490	492	0.40	0.08	11	1	10	22	0.1	97	AS7-5695a
M-07-54	X10347	492	494	0.78	0.29	6	3.4	10	24	0.1	79	AS7-5695a
M-07-54	X10348	494	496	1.07	0.44	6	5.4	15	14	0.1	65	AS7-5695a
M-07-54	X10349	496	498	0.57	0.22	9	5.1	15	16	0.1	106	AS7-5695a
M-07-54	X10350	498	500	0.55	0.18	15	8	15	40	0.1	37	AS7-5695a
M-07-54	X10352	500	502	0.51	0.09	10	1.3	15	8	0.1	85	AS7-5695a
M-07-54	X10353	502	504	0.60	0.29	9	3.2	10	34	0.1	107	AS7-5695a
M-07-54	X10355	504	506	0.74	0.18	9	2.1	10	18	0.1	71	AS7-5695a
M-07-54	X10356	506	508	0.43	0.09	7	1.2	10	14	0.1	55	AS7-5695a
M-07-54	X10357	508	510	0.54	0.17	14	1.9	0.1	28	0.1	54	AS7-5691a
M-07-54	X10358	510	512	0.33	0.11	12	1.4	0.1	52	10	73	AS7-5691a
M-07-54	X10359	512	514	0.47	0.16	11	2.1	0.1	50	0.1	84	AS7-5691a
M-07-54	X10360	514	516	0.31	0.11	11	2.3	0.1	44	15	79	AS7-5691a
M-07-54	X10361	516	518	0.37	0.15	11	2.1	0.1	58	10	115	AS7-5691a
M-07-54	X10362	518	520	0.71	0.11	15	2	0.1	70	10	609	AS7-5691a
M-07-54	X10363	520	522	0.54	0.14	11	2.9	10	36	10	111	AS7-5691a
M-07-54	X10364	522	524	0.51	0.19	17	5.9	0.1	72	25	139	AS7-5691a
M-07-54	X10365	524	526	0.36	0.12	12	2.5	0.1	38	10	85	AS7-5691a
M-07-54	X10366	526	528	0.28	0.13	13	2.2	0.1	28	5	58	AS7-5691a
M-07-54	X10367	528	530	0.51	0.15	11	2.8	0.1	26	15	58	AS7-5691a
M-07-54	X10368	530	532	0.36	0.18	9	4.2	25	42	10	26	AS7-5691a
M-07-54	X10369	532	534	0.54	0.15	12	4.8	85	24	5	37	AS7-5691a
M-07-54	X10370	534	536	0.35	0.26	14	3.4	0.1	26	10	44	AS7-5691a
M-07-54	X10371	536	538	0.39	0.13	11	2.2	5	28	10	55	AS7-5691a
M-07-54	X10372	538	540	0.83	0.25	10	3.2	0.1	34	10	41	AS7-5691a
M-07-54	X10373	540	542	0.49	0.11	14	2.6	60	34	15	63	AS7-5691a
M-07-54	X10374	542	544.28	0.34	0.08	11	2.9	25	38	20	61	AS7-5691a
M-07-54	X10375	544.28	544.85	0.09	0.01	14	1.8	0.1	90	45	147	AS7-5691a
M-07-54	X10376	544.85	546	0.54	0.07	11	3.1	160	36	15	48	AS7-5691a
M-07-54	X10377	546	548	0.27	0.07	10	1.9	50	38	15	57	AS7-5691a
M-07-54	X10378	548	550	0.29	0.08	13	2.6	0.1	40	15	65	AS7-5691a
M-07-54	X10379	550	552	0.50	0.52	10	10.9	40	32	10	36	AS7-5691a
M-07-54	X10380	552	554	0.56	0.31	7	45.7	45	118	35	89	AS7-5691a
M-07-54	X10381	554	556	0.60	0.31	10	185	125	390	220	103	AS7-5691a
M-07-54	X10383	556	558	0.08	0.14	7	2.4	0.1	42	0.1	89	AS7-5691a
M-07-54	X10384	558	560	0.36	0.12	8	2.4	0.1	28	10	57	AS7-5691a
M-07-54	X10385	560	562	0.55	0.05	11	1.7	0.1	30	20	85	AS7-5691a
M-07-54	X10387	562	564	0.43	0.12	8	4.2	10	28	0.1	65	AS7-5691a
M-07-54	X10388	564	566	0.82	0.10	10	5.4	0.1	56	0.1	20	AS7-5691a
M-07-54	X10389	566	568	0.48	0.14	10	3.2	0.1	38	5	116	AS7-5691a
M-07-54	X10390	568	570	0.53	0.12	9	4	55	30	25	32	AS7-5691a
M-07-54	X10391	570	572	0.68	0.15	12	3.4	40	36	15	86	AS7-5691a
M-07-54	X10392	572	574	0.70	0.21	13	6.7	10	42	10	32	AS7-5694a
M-07-54	X10393	574	576.15	0.71	0.36	11	11.1	65	46	0.1	36	AS7-5694a
M-07-54	X10394	576.15	578	0.05	0.00	10	0.2	30	70	40	148	AS7-5694a
M-07-54	X10395	578	579.4	0.00	0.00	14	0.2	40	60	65	137	AS7-5694a
M-07-54	X10396	579.4	581	0.54	0.07	9	2.8	30	30	20	55	AS7-5694a
M-07-54	X10397	581	582.23	0.26	0.06	7	2.1	85	44	15	81	AS7-5694a
M-07-54	X10398	582.23	584.35	0.04	0.01	12	0.6	75	90	45	230	AS7-5694a
M-07-54	X10399	584.35	586.48	0.06	0.03	10	0.9	60	66	45	180	AS7-5694a
M-07-54	X10400	586.48	588	0.29	0.07	11	2.8	30	32	20	70	AS7-5694a
M-07-54	X10401	588	590	0.50	0.20	9	4.1	60	28	15	61	AS7-5694a
M-07-54	X10402	590	592	0.52	0.14	13	2.7	0.1	38	20	79	AS7-5694a
M-07-54	X10403	592	594	0.65	0.16	13	2.8	30	38	25	65	AS7-5694a
M-07-54	X10404	594	596	0.88	0.21	11	8.1	35	130	20	85	AS7-5694a
M-07-54	X10405	596	598	0.41	0.15	12	3.8	30	38	35	72	AS7-5694a
M-07-54	X10406	598	600	0.17	0.06	14	1.9	15	44	30	95	AS7-5694a
M-07-54	X10407	600	602	0.74	0.21	12	3.4	5	36	20	83	AS7-5694a
M-07-54	X10408	602	604	0.45	0.15	12	2.6	20	36	25	66	AS7-5694a
M-07-54	X10409	604	606	0.55	0.23	11	3.5	0.1	32	20	58	AS7-5694a
M-07-54	X10410	606	608	0.62	0.20	12	3.6	0.1	34	20	54	AS7-5694a
M-07-54	X10411	608	610.1	0.49	0.13	11	2.5	25	30	25	58	AS7-5694a
M-07-54	X10413	610.1	612.3	0.45	0.18	11	4.4	15	32	25	46	AS7-5694a
M-07-54	X10414	612.3	614.3	0.34	0.13	11	4.2	35	40	20	21	AS7-5694a
M-07-54	X10415	614.3	616.3	0.33	0.17	11	4.6	30	38	15	22	AS7-5694a
M-07-54	X10416	616.3	618	0.52	0.26	11	3.9	35	40	10	45	AS7-5694a
M-07-54	X10417	618	620	0.82	0.21	13	2.5	110	50	20	58	AS7-5694a
M-07-54	X10418	620	622	0.75	0.25	11	2.6	25	36	15	56	AS7-5694a
M-07-54	X10420	622	624	0.40	0.19	11	2.4	0.1	32	25	52	AS7-5694a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-54	X10421	624	626	0.39	0.19	11	2.5	0.1	32	15	49	AS7-5694a
M-07-54	X10422	626	628	0.29	0.17	13	2.7	0.1	38	20	68	AS7-5694a
M-07-54	X10424	628	630	0.32	0.15	14	2	0.1	42	30	64	AS7-5694a
M-07-54	X10425	630	632	0.39	0.19	12	2.4	0.1	38	25	52	AS7-5694a
M-07-54	X10426	632	634	0.45	0.19	11	2.4	0.1	36	25	45	AS7-5694a
M-07-54	X10427	634	636	0.74	0.24	12	3.4	0.1	34	20	59	AS7-5717a
M-07-54	X10428	636	638	0.79	0.25	12	3.2	0.1	30	15	53	AS7-5717a
M-07-54	X10429	638	640	1.27	0.34	10	3.6	0.1	34	10	52	AS7-5717a
M-07-54	X10430	640	642	1.01	0.37	12	3.9	0.1	36	15	50	AS7-5717a
M-07-54	X10431	642	644	1.01	0.18	10	2.4	0.1	32	10	59	AS7-5717a
M-07-54	X10432	644	646	0.65	0.20	12	2.9	0.1	32	10	55	AS7-5717a
M-07-54	X10433	646	648	1.62	0.31	12	4.2	0.1	38	20	56	AS7-5717a
M-07-54	X10434	648	650	0.64	0.20	12	3	0.1	32	10	51	AS7-5717a
M-07-54	X10435	650	652	0.45	0.13	10	2.1	5	32	10	42	AS7-5717a
M-07-54	X10436	652	654	0.45	0.11	14	2.2	0.1	36	10	29	AS7-5717a
M-07-54	X10437	654	656	0.51	0.10	17	1.5	20	34	30	34	AS7-5717a
M-07-54	X10438	656	658	0.27	0.13	12	1.4	0.1	38	15	57	AS7-5717a
M-07-54	X10439	658	660	0.40	0.10	11	1.4	0.1	38	20	52	AS7-5717a
M-07-54	X10440	660	662	0.40	0.11	12	1.5	15	34	10	52	AS7-5717a
M-07-54	X10441	662	664	0.49	0.17	11	2.2	10	32	10	43	AS7-5717a
M-07-54	X10442	664	666	0.55	0.19	12	2.3	10	34	15	49	AS7-5717a
M-07-54	X10443	666	668	0.32	0.12	12	1.7	10	32	10	37	AS7-5717a
M-07-54	X10444	668	669.2	0.37	0.16	10	1.9	0.1	30	0.1	41	AS7-5717a
M-07-54	X10445	669.2	670.45	0.36	0.14	11	1.9	10	36	15	54	AS7-5717a
M-07-55	X05574	6.1	8	0.71	0.20	15	2.8	20	16	0.1	91	AS7-5705a
M-07-55	X05575	8	10	0.61	0.16	20	2.4	25	16	0.1	90	AS7-5705a
M-07-55	X05576	10	12	0.70	0.17	20	2.4	30	18	0.1	69	AS7-5705a
M-07-55	X05577	12	14	0.74	0.17	19	2.5	25	16	0.1	68	AS7-5705a
M-07-55	X05578	14	16	0.99	0.27	18	3.8	25	20	0.1	46	AS7-5705a
M-07-55	X05581	16	18	0.97	0.23	15	3.5	25	16	0.1	70	AS7-5705a
M-07-55	X05582	18	20	0.84	0.24	22	3.3	40	18	0.1	42	AS7-5705a
M-07-55	X05583	20	22	0.97	0.21	25	3.4	30	18	0.1	60	AS7-5705a
M-07-55	X05584	22	24	0.97	0.18	22	3.6	55	18	0.1	72	AS7-5705a
M-07-55	X05585	24	26	1.08	0.27	22	6.1	130	34	5	37	AS7-5705a
M-07-55	X05586	26	28	0.93	0.18	20	2.9	50	12	0.1	63	AS7-5705a
M-07-55	X05587	28	30	1.25	0.33	17	4.4	20	12	0.1	61	AS7-5705a
M-07-55	X05588	30	32	1.86	0.31	24	6.6	115	44	0.1	35	AS7-5702a
M-07-55	X05589	32	34	1.01	0.19	29	4	45	42	15	69	AS7-5702a
M-07-55	X05590	34	36	0.77	0.19	25	3.5	15	40	10	69	AS7-5702a
M-07-55	X05592	36	38	0.61	0.16	31	3	10	40	10	76	AS7-5702a
M-07-55	X05594	38	40	0.88	0.24	41	4.3	0.1	38	10	60	AS7-5702a
M-07-55	X05595	40	42	0.64	0.15	26	2.5	0.1	38	10	68	AS7-5702a
M-07-55	X05596	42	44	0.75	0.22	25	4.5	10	40	10	51	AS7-5702a
M-07-55	X05597	44	46	1.01	0.26	28	5.4	25	34	10	38	AS7-5702a
M-07-55	X05598	46	48	0.91	0.20	28	4.2	35	36	25	56	AS7-5702a
M-07-55	X05599	48	50	1.54	0.33	23	5.5	40	46	10	58	AS7-5702a
M-07-55	X05600	50	52	1.58	0.23	23	3.8	20	38	5	63	AS7-5702a
M-07-55	X05601	52	54	0.75	0.18	20	3.3	20	48	10	81	AS7-5702a
M-07-55	X05602	54	56	1.20	0.26	20	3.7	15	44	0.1	66	AS7-5702a
M-07-55	X05603	56	58	0.89	0.18	22	3.1	10	50	15	116	AS7-5702a
M-07-55	X05604	58	60	0.88	0.23	33	3.1	15	44	15	68	AS7-5702a
M-07-55	X05605	60	62	1.12	0.26	21	4.1	0.1	48	10	67	AS7-5702a
M-07-55	X05606	62	64	0.96	0.21	32	3.1	0.1	38	15	68	AS7-5702a
M-07-55	X05607	64	66	0.64	0.15	23	2.8	0.1	40	5	73	AS7-5702a
M-07-55	X05608	66	68	0.63	0.14	29	2.6	0.1	48	15	86	AS7-5702a
M-07-55	X05609	68	70	0.75	0.15	29	2.3	10	46	30	73	AS7-5702a
M-07-55	X05610	70	72	0.83	0.23	36	3.1	5	44	35	64	AS7-5702a
M-07-55	X05612	72	74	0.88	0.23	34	3.3	5	40	20	43	AS7-5702a
M-07-55	X05613	74	76	0.86	0.22	32	3	5	44	15	61	AS7-5702a
M-07-55	X05614	76	78	0.75	0.18	31	2.4	5	50	20	71	AS7-5702a
M-07-55	X05615	78	80	0.88	0.22	27	2.9	0.1	46	10	78	AS7-5702a
M-07-55	X05616	80	82	1.01	0.22	25	3.8	20	40	10	48	AS7-5702a
M-07-55	X05617	82	84	1.06	0.25	21	4.6	30	42	0.1	20	AS7-5702a
M-07-55	X05618	84	86	1.16	0.20	24	3.5	30	42	0.1	28	AS7-5702a
M-07-55	X05619	86	88	1.24	0.32	34	4.6	10	38	15	50	AS7-5702a
M-07-55	X05620	88	90	0.94	0.27	35	3.3	10	36	25	48	AS7-5702a
M-07-55	X05621	90	92	0.86	0.19	19	2.3	10	48	10	54	AS7-5702a
M-07-55	X05622	92	94	0.77	0.19	21	2.6	5	42	20	71	AS7-5702a
M-07-55	X05623	94	96	0.99	0.19	22	3.1	10	50	10	77	AS7-5709a
M-07-55	X05624	96	98	0.84	0.22	24	2.9	5	46	15	88	AS7-5709a
M-07-55	X05625	98	100	1.28	0.29	24	4.3	10	44	10	83	AS7-5709a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-55	X05626	100	101.57	0.53	0.16	27	2.5	15	54	25	94	AS7-5709a
M-07-55	X05627	101.57	103.75	0.00	0.00	10	0.2	10	76	35	95	AS7-5709a
M-07-55	X05628	103.75	105	0.74	0.21	19	3.3	15	48	20	85	AS7-5709a
M-07-55	X05629	105	107	0.85	0.24	26	3.3	10	52	20	114	AS7-5709a
M-07-55	X05630	107	109	0.83	0.19	21	3	15	48	10	96	AS7-5709a
M-07-55	X05631	109	111	0.90	0.26	33	4.9	30	48	10	61	AS7-5709a
M-07-55	X05632	111	113	0.61	0.16	24	2.3	10	52	15	117	AS7-5709a
M-07-55	X05634	113	115	0.86	0.22	33	3.7	5	56	10	107	AS7-5709a
M-07-55	X05635	115	117	0.47	0.14	22	2.6	0.1	62	15	116	AS7-5709a
M-07-55	X05636	117	119	0.89	0.24	21	4.5	30	52	10	83	AS7-5709a
M-07-55	X05637	119	120.6	0.84	0.24	22	3.9	20	50	15	83	AS7-5709a
M-07-55	X05638	121.6	123	0.86	0.23	19	4.5	30	40	0.1	37	AS7-5709a
M-07-55	X05640	123	125	0.63	0.21	39	4	20	48	5	87	AS7-5709a
M-07-55	X05641	125	127	0.71	0.23	22	4.3	15	54	15	93	AS7-5709a
M-07-55	X05642	127	129	1.38	0.40	26	6.2	10	50	30	86	AS7-5709a
M-07-55	X05644	129	131	0.73	0.24	18	3.8	10	58	5	101	AS7-5709a
M-07-55	X05645	131	133	0.90	0.23	28	4.6	30	58	0.1	58	AS7-5709a
M-07-55	X05646	133	135	0.76	0.22	24	3.2	10	66	25	93	AS7-5709a
M-07-55	X05647	135	137	0.82	0.27	18	4.8	10	56	15	105	AS7-5709a
M-07-55	X05648	137	139	1.09	0.37	16	5	10	52	20	107	AS7-5709a
M-07-55	X05649	139	141	1.02	0.37	21	5.2	10	60	15	115	AS7-5709a
M-07-55	X05650	141	143	0.81	0.23	25	3.9	20	46	15	74	AS7-5709a
M-07-55	X05651	143	145	0.97	0.26	25	4	10	40	10	61	AS7-5709a
M-07-55	X05652	145	147	1.16	0.34	116	5.1	15	34	0.1	51	AS7-5709a
M-07-55	X05653	147	149	1.57	0.49	25	6.2	15	40	0.1	74	AS7-5709a
M-07-55	X05654	149	151	0.89	0.28	16	3.9	0.1	42	15	80	AS7-5709a
M-07-55	X05655	151	153	0.76	0.24	136	4.3	20	36	0.1	54	AS7-5709a
M-07-55	X05656	153	155	0.66	0.20	18	3.7	15	46	0.1	95	AS7-5709a
M-07-55	X05657	155	157	1.02	0.29	22	4.7	15	50	10	92	AS7-5709a
M-07-55	X05659	157	159	0.87	0.25	27	4.1	5	38	15	68	AS7-5707a
M-07-55	X05660	159	161	0.82	0.23	45	3.7	0.1	58	0.1	65	AS7-5707a
M-07-55	X05661	161	163	0.93	0.27	31	4.9	0.1	46	15	104	AS7-5707a
M-07-55	X05662	163	165	0.66	0.21	20	3.8	0.1	48	5	82	AS7-5707a
M-07-55	X05663	165	167	1.04	0.40	34	4.6	0.1	42	15	104	AS7-5707a
M-07-55	X05664	167	169	0.82	0.24	18	3.5	0.1	46	10	88	AS7-5707a
M-07-55	X05665	169	171	0.68	0.19	26	2.8	0.1	46	10	64	AS7-5707a
M-07-55	X05666	171	173	0.68	0.18	21	3.9	0.1	40	0.1	85	AS7-5707a
M-07-55	X05667	173	175	0.82	0.18	17	3.4	10	32	0.1	59	AS7-5707a
M-07-55	X05668	175	176.4	0.62	0.16	28	2.6	15	38	25	91	AS7-5707a
M-07-55	X05669	176.4	177.65	0.69	0.17	20	2	0.1	40	20	91	AS7-5707a
M-07-55	X05670	178.5	179	0.36	0.15	20	1.7	0.1	86	5	99	AS7-5707a
M-07-55	X05671	179	181	0.53	0.16	19	3.3	0.1	38	15	88	AS7-5707a
M-07-55	X05672	181	183	0.62	0.13	17	1.4	0.1	34	10	85	AS7-5707a
M-07-55	X05673	183	185	0.81	0.18	14	1.8	0.1	42	20	103	AS7-5707a
M-07-55	X05674	185	187	0.44	0.15	17	1.4	0.1	34	20	73	AS7-5707a
M-07-55	X05675	187	189	1.12	0.11	14	1.5	0.1	38	0.1	63	AS7-5707a
M-07-55	X05676	189	191	1.02	0.10	17	1.5	0.1	256	10	121	AS7-5707a
M-07-55	X05677	191	193	0.33	0.10	20	1.2	0.1	58	40	93	AS7-5707a
M-07-55	X05679	193	195	0.19	0.05	15	0.6	0.1	46	20	54	AS7-5707a
M-07-55	X05680	195	197	0.22	0.07	13	0.7	0.1	38	20	73	AS7-5707a
M-07-55	X05681	197	199	0.23	0.08	14	0.8	0.1	26	5	41	AS7-5707a
M-07-55	X05682	199	201	0.44	0.15	12	1.7	5	28	15	50	AS7-5707a
M-07-55	X05683	201	203	0.38	0.11	13	1.2	0.1	32	5	61	AS7-5707a
M-07-55	X05684	203	205	0.43	0.14	12	1.5	0.1	32	5	78	AS7-5707a
M-07-55	X05685	205	207	0.64	0.19	24	1.9	0.1	24	10	40	AS7-5707a
M-07-55	X05686	207	209	0.51	0.14	20	1.3	0.1	24	5	42	AS7-5707a
M-07-55	X05687	209	211	0.62	0.28	13	2.7	0.1	30	10	47	AS7-5707a
M-07-55	X05688	211	213	0.26	0.08	14	0.6	0.1	24	0.1	39	AS7-5707a
M-07-55	X05689	213	215	0.30	0.07	13	0.7	0.1	28	10	65	AS7-5707a
M-07-55	X05690	215	217	0.37	0.12	17	1.3	0.1	52	15	63	AS7-5707a
M-07-55	X05691	217	219	0.45	0.15	15	1.2	0.1	38	0.1	60	AS7-5707a
M-07-55	X05692	219	221	0.47	0.17	19	1.5	0.1	34	15	83	AS7-5707a
M-07-55	X05693	221	223	0.41	0.12	13	1	15	42	20	94	AS7-5744a
M-07-55	X05694	223	225	0.52	0.16	14	3.3	25	44	20	91	AS7-5744a
M-07-55	X05695	225	227	0.40	0.10	19	1.1	20	34	20	81	AS7-5744a
M-07-55	X05697	227	229	0.49	0.14	11	1.4	15	36	0.1	75	AS7-5744a
M-07-55	X05698	229	231	0.45	0.16	14	1.5	20	40	15	94	AS7-5744a
M-07-55	X05699	231	233	0.83	0.36	13	4.1	35	100	15	157	AS7-5744a
M-07-55	X05700	233	235	0.55	0.12	20	1.8	35	50	15	132	AS7-5744a
M-07-55	X05701	235	237	1.23	0.15	15	2.8	45	46	5	89	AS7-5744a
M-07-55	X05702	237	239	0.83	0.14	16	3.1	50	80	0.1	30	AS7-5744a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-55	X05703	239	241	2.21	0.41	12	5	65	52	0.1	61	AS7-5744a
M-07-55	X05704	241	243	1.45	0.10	14	2	45	44	5	61	AS7-5744a
M-07-55	X05706	243	245	0.54	0.14	15	1.7	20	34	5	91	AS7-5744a
M-07-55	X05707	245	247	0.34	0.11	12	1.2	15	38	10	104	AS7-5744a
M-07-55	X05708	247	249	0.19	0.07	13	0.7	10	38	10	79	AS7-5744a
M-07-55	X05709	249	251	0.65	0.21	11	2	15	46	5	89	AS7-5744a
M-07-55	X05710	251	253	0.79	0.31	17	3.5	30	50	35	94	AS7-5744a
M-07-55	X05711	253	255	1.45	0.31	11	3.7	15	36	0.1	87	AS7-5744a
M-07-55	X05712	255	257	0.37	0.14	14	1.7	10	44	0.1	102	AS7-5744a
M-07-55	X05713	257	259	0.42	0.13	12	1.4	30	42	5	95	AS7-5744a
M-07-55	X05714	259	261	0.34	0.11	15	1.5	15	34	10	76	AS7-5744a
M-07-55	X05715	261	263	0.63	0.23	10	3.4	30	38	10	92	AS7-5744a
M-07-55	X05717	263	265	0.84	0.21	15	3	40	44	15	91	AS7-5744a
M-07-55	X05718	265	267	0.60	0.20	15	2.6	30	50	25	96	AS7-5744a
M-07-55	X05719	267	269	0.50	0.13	15	1.8	20	40	15	85	AS7-5744a
M-07-55	X05720	269	271	0.54	0.07	11	1.1	30	44	10	88	AS7-5744a
M-07-55	X05721	271	273	0.38	0.09	13	2	40	50	10	94	AS7-5744a
M-07-55	X05722	273	275	0.38	0.17	11	4.8	40	62	15	89	AS7-5744a
M-07-55	X05723	275	277	0.41	0.12	13	2.1	45	48	15	82	AS7-5744a
M-07-55	X05724	277	279	0.29	0.10	9	1.2	35	40	10	87	AS7-5744a
M-07-55	X05725	279	281	0.56	0.19	11	2.1	25	48	10	66	AS7-5744a
M-07-55	X05726	281	283	0.48	0.17	9	1.9	15	46	10	63	AS7-5744a
M-07-55	X05727	283	285	0.35	0.12	10	1.5	25	34	10	67	AS7-5744a
M-07-55	X05728	285	287	1.17	0.34	16	3.5	0.1	26	30	65	AS7-5696a
M-07-55	X05730	287	289	0.76	0.25	16	2.4	0.1	26	20	72	AS7-5696a
M-07-55	X05731	289	291	0.35	0.10	12	1.2	0.1	26	10	64	AS7-5696a
M-07-55	X05732	291	292.25	0.28	0.05	12	1.1	15	28	15	58	AS7-5696a
M-07-55	X05733	292.25	293.5	0.36	0.12	12	1.4	0.1	24	10	55	AS7-5696a
M-07-55	X05734	293.5	295	0.35	0.11	11	1.3	0.1	26	10	62	AS7-5696a
M-07-55	X05735	295	297	0.37	0.11	11	1.1	0.1	28	5	58	AS7-5696a
M-07-55	X05736	297	299	0.25	0.07	12	0.8	0.1	28	5	61	AS7-5696a
M-07-55	X05737	299	301	0.30	0.09	13	1.1	0.1	28	15	64	AS7-5696a
M-07-55	X05738	301	303	0.26	0.11	14	1.7	0.1	32	15	49	AS7-5696a
M-07-55	X05739	303	305	0.24	0.06	18	1.2	0.1	34	15	78	AS7-5696a
M-07-55	X05740	305	307	0.16	0.05	10	0.7	0.1	28	0.1	57	AS7-5696a
M-07-55	X05742	307	309	0.95	0.19	10	2.7	5	32	5	64	AS7-5696a
M-07-55	X05743	309	310.5	1.35	0.61	15	7.4	15	52	20	78	AS7-5696a
M-07-55	X05744	310.5	311.7	0.41	0.12	29	2.4	0.1	32	10	74	AS7-5696a
M-07-55	X05745	312.71	314	0.48	0.09	15	2.7	5	42	5	71	AS7-5696a
M-07-55	X05746	314	316	0.29	0.08	15	3.4	5	36	5	81	AS7-5696a
M-07-55	X05747	316	318	0.42	0.08	18	3	10	38	20	106	AS7-5696a
M-07-55	X05749	318	320	0.42	0.11	37	5	5	84	20	154	AS7-5696a
M-07-55	X05750	320	322	0.18	0.05	25	0.8	0.1	36	10	95	AS7-5696a
M-07-55	X05751	322	324	0.42	0.13	18	1.9	0.1	40	10	108	AS7-5696a
M-07-55	X05752	324	325.25	0.44	0.24	26	3.6	0.1	30	10	142	AS7-5696a
M-07-55	X05753	325.25	327	0.33	0.10	17	1.1	0.1	30	10	73	AS7-5696a
M-07-55	X05754	327	329	0.44	0.36	26	3.4	0.1	32	10	58	AS7-5696a
M-07-55	X05755	329	331	0.34	0.11	24	1.1	0.1	58	5	88	AS7-5696a
M-07-55	X05756	331	333	0.29	0.09	244	0.6	5	30	0.1	62	AS7-5696a
M-07-55	X05757	333	335	0.31	0.11	25	0.8	0.1	34	15	78	AS7-5696a
M-07-55	X05758	335	337.1	0.50	0.10	25	0.8	0.1	24	10	60	AS7-5696a
M-07-55	X05759	337.1	339	0.51	0.22	48	2.1	15	30	15	66	AS7-5696a
M-07-55	X05760	339	341	0.58	0.18	18	1.6	10	30	25	78	AS7-5696a
M-07-55	X05761	341	343	0.59	0.19	218	1.6	10	26	10	48	AS7-5696a
M-07-55	X05762	343	345	0.61	0.20	67	1.7	0.1	28	0.1	40	AS7-5696a
M-07-55	X05763	345	346.5	0.38	0.25	25	2.6	30	44	15	61	AS7-5745a
M-07-55	X05764	346.5	347.45	0.31	0.15	19	3.7	30	38	10	73	AS7-5745a
M-07-55	X05765	347.45	348.7	1.12	0.71	11	10.5	30	62	10	42	AS7-5745a
M-07-55	X05767	348.7	349.95	0.50	0.44	50	5.7	30	52	10	48	AS7-5745a
M-07-55	X05768	349.95	352	0.32	0.13	24	2	35	40	15	59	AS7-5745a
M-07-55	X05770	352	354	0.45	0.19	79	2.7	40	38	10	70	AS7-5745a
M-07-55	X05771	354	356	0.41	0.16	74	6.1	40	40	10	100	AS7-5745a
M-07-55	X05772	356	358	0.49	0.19	62	6	45	86	25	140	AS7-5745a
M-07-55	X05773	358	360	0.39	0.14	43	1.7	55	58	0.1	222	AS7-5745a
M-07-55	X05774	360	362	0.30	0.12	28	1.1	30	40	5	92	AS7-5745a
M-07-55	X05775	362	364	0.16	0.06	35	0.9	30	36	15	82	AS7-5745a
M-07-55	X05776	364	366	0.48	0.26	85	2.5	35	56	10	103	AS7-5745a
M-07-55	X05777	366	368	0.23	0.12	21	1.2	30	42	5	65	AS7-5745a
M-07-55	X05778	368	370	0.38	0.17	92	3.2	30	56	0.1	531	AS7-5745a
M-07-55	X05779	370	372	0.25	0.13	47	1.4	30	38	15	80	AS7-5745a
M-07-55	X05781	372	374	0.18	0.07	38	1.4	40	38	10	69	AS7-5745a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-55	X05782	374	376	0.80	0.21	71	2.7	35	42	15	72	AS7-5745a
M-07-55	X05783	376	378	0.55	0.22	208	2.5	40	38	15	79	AS7-5745a
M-07-55	X05784	378	380	0.34	0.17	45	2.2	30	50	20	226	AS7-5745a
M-07-55	X05785	380	382	0.36	0.14	138	1.9	45	50	5	101	AS7-5745a
M-07-55	X05786	382	384	0.39	0.11	57	2.4	30	46	5	84	AS7-5745a
M-07-55	X05787	384	386	0.36	0.14	32	2.3	30	36	5	62	AS7-5745a
M-07-55	X05788	386	388	0.35	0.10	67	1.3	35	40	5	56	AS7-5745a
M-07-55	X05789	388	390	0.32	0.12	38	2.8	30	52	10	60	AS7-5745a
M-07-55	X05790	390	392	0.50	0.15	68	2.7	45	58	0.1	97	AS7-5745a
M-07-55	X05791	392	394	0.36	0.15	113	2.5	55	80	10	442	AS7-5745a
M-07-55	X05792	394	396	0.28	0.12	156	1.7	40	50	10	74	AS7-5745a
M-07-55	X05793	396	398	0.26	0.12	134	2.1	35	98	10	147	AS7-5745a
M-07-55	X05794	398	400	0.27	0.11	153	1.5	40	52	5	103	AS7-5745a
M-07-55	X05795	400	402	0.26	0.12	33	1.7	35	56	20	236	AS7-5745a
M-07-55	X05796	402	404	0.21	0.08	94	1.7	50	32	10	68	AS7-5745a
M-07-55	X05797	404	406	0.50	0.11	106	2.6	60	104	5	282	AS7-5745a
M-07-55	X05798	406	408	0.41	0.16	885	1.5	25	38	5	68	AS7-5710a
M-07-55	X05799	408	410	0.39	0.18	127	1.5	15	34	10	56	AS7-5710a
M-07-55	X05800	410	412.1	0.37	0.14	257	1.2	20	32	5	47	AS7-5710a
M-07-55	X05801	412.1	414.2	0.25	0.10	285	0.9	20	36	0.1	77	AS7-5710a
M-07-56	X14001	4.57	6	0.59	0.12	80	1.5	0.1	112	15	341	AS7-5701a
M-07-56	X14002	6	8	0.69	0.12	136	1.8	0.1	130	15	322	AS7-5701a
M-07-56	X14003	8	10	1.01	0.13	161	1.8	0.1	60	20	234	AS7-5701a
M-07-56	X14004	10	12	0.96	0.17	96	1.5	0.1	48	20	178	AS7-5701a
M-07-56	X14005	12	14	0.67	0.11	92	1.3	0.1	54	20	297	AS7-5701a
M-07-56	X14006	14	16	0.67	0.13	130	1.8	0.1	72	5	180	AS7-5701a
M-07-56	X14007	16	18	0.49	0.12	111	2	5	100	5	219	AS7-5701a
M-07-56	X14008	18	20	0.78	0.14	108	2	15	162	15	565	AS7-5701a
M-07-56	X14009	20	22	0.59	0.13	187	2.1	10	106	15	315	AS7-5701a
M-07-56	X14010	22	24	0.67	0.14	130	2.6	15	116	15	379	AS7-5701a
M-07-56	X14011	24	26	0.73	0.16	205	1.9	10	258	10	303	AS7-5701a
M-07-56	X14012	26	28	0.70	0.13	129	1.4	20	84	10	276	AS7-5701a
M-07-56	X14013	28	30	0.84	0.12	148	1.6	5	92	15	332	AS7-5701a
M-07-56	X14014	30	32	0.44	0.11	76	1.3	5	106	10	310	AS7-5701a
M-07-56	X14015	32	34	1.05	0.11	138	1.8	10	92	25	358	AS7-5701a
M-07-56	X14016	34	36	0.83	0.14	141	1.8	15	124	20	235	AS7-5701a
M-07-56	X14017	36	38	0.93	0.12	564	1.3	15	104	20	298	AS7-5701a
M-07-56	X14018	38	40	1.04	0.16	135	2	10	130	15	407	AS7-5701a
M-07-56	X14019	40	42	0.83	0.18	292	3.3	20	422	15	940	AS7-5701a
M-07-56	X14020	42	44	0.87	0.13	174	1.7	15	118	5	255	AS7-5701a
M-07-56	X14021	44	46.4	0.66	0.13	97	1.7	5	110	45	259	AS7-5701a
M-07-56	X14022	46.4	48	0.94	0.14	99	1.9	25	86	0.1	440	AS7-5701a
M-07-56	X14023	48	50	0.72	0.16	76	2.8	5	118	15	341	AS7-5701a
M-07-56	X14024	50	52	0.88	0.14	83	2.1	5	84	20	311	AS7-5701a
M-07-56	X14025	52	54	0.77	0.14	120	2.2	20	182	0.1	422	AS7-5701a
M-07-56	X14026	54	56	0.81	0.17	161	1.9	15	154	25	468	AS7-5701a
M-07-56	X14027	56	58	0.71	0.14	105	1.9	5	292	10	539	AS7-5701a
M-07-56	X14028	58	60	0.76	0.16	109	2	0.1	156	10	784	AS7-5701a
M-07-56	X14029	60	61.75	0.60	0.16	182	1.6	10	68	15	264	AS7-5701a
M-07-56	X14030	61.75	64	0.26	0.13	115	1.9	40	94	10	187	AS7-5701a
M-07-56	X14033	64	66	0.86	0.14	127	1.8	10	114	10	218	AS7-5701a
M-07-56	X14034	66	68	0.83	0.14	113	1.4	10	50	15	238	AS7-5701a
M-07-56	X14036	68	70	0.72	0.15	49	2	15	144	0.1	183	AS7-5743a
M-07-56	X14037	70	72	0.44	0.14	66	1.6	0.1	86	0.1	281	AS7-5743a
M-07-56	X14038	72	74	0.93	0.16	88	1.9	10	44	0.1	231	AS7-5743a
M-07-56	X14039	74	76	1.02	0.21	61	2.9	15	86	0.1	371	AS7-5743a
M-07-56	X14040	76	78	0.82	0.13	78	1.4	20	58	0.1	182	AS7-5743a
M-07-56	X14041	78	80	0.73	0.16	135	1.3	20	52	5	121	AS7-5743a
M-07-56	X14042	80	82	0.49	0.16	103	1.5	75	42	20	69	AS7-5743a
M-07-56	X14043	82	84	0.55	0.14	102	1.1	40	42	10	91	AS7-5743a
M-07-56	X14044	84	86	0.48	0.11	117	1.6	45	72	0.1	177	AS7-5743a
M-07-56	X14045	86	88	0.45	0.12	100	1.5	15	170	0.1	308	AS7-5743a
M-07-56	X14046	88	90	0.85	0.17	123	1.9	20	62	0.1	156	AS7-5743a
M-07-56	X14047	90	92	0.90	0.16	134	2.3	15	88	10	227	AS7-5743a
M-07-56	X14048	92	94	0.51	0.14	75	2.1	15	94	10	230	AS7-5743a
M-07-56	X14049	94	96	0.66	0.12	71	1.8	5	82	5	262	AS7-5743a
M-07-56	X14050	96	98	1.01	0.14	113	2.4	5	76	10	267	AS7-5743a
M-07-56	X14051	98	100	0.85	0.18	54	2.6	10	116	0.1	400	AS7-5743a
M-07-56	X14052	100	102	0.58	0.16	60	2.2	0.1	102	0.1	269	AS7-5743a
M-07-56	X14053	102	104	0.89	0.13	101	1.9	15	62	15	197	AS7-5743a
M-07-56	X14055	104	106	1.14	0.17	52	2.3	5	62	0.1	159	AS7-5743a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-56	X14056	106	108	1.47	0.20	52	2.9	10	56	0.1	209	AS7-5743a
M-07-56	X14057	108	110	1.57	0.23	74	3	0.1	56	10	280	AS7-5743a
M-07-56	X14058	110	112	1.12	0.18	80	2.4	0.1	78	0.1	281	AS7-5743a
M-07-56	X14059	112	114	1.23	0.20	60	2.7	20	90	10	251	AS7-5743a
M-07-56	X14060	114	116	1.06	0.19	65	2.5	0.1	100	0.1	232	AS7-5743a
M-07-56	X14061	116	118	0.84	0.14	57	2.1	0.1	92	0.1	230	AS7-5743a
M-07-56	X14062	118	120	0.99	0.16	117	2.6	5	104	0.1	212	AS7-5743a
M-07-56	X14063	120	122	0.81	0.11	62	2.2	0.1	78	0.1	199	AS7-5743a
M-07-56	X14065	122	124	0.85	0.14	48	2	10	86	0.1	117	AS7-5743a
M-07-56	X14066	124	126	0.82	0.20	75	3.3	50	86	30	173	AS7-5743a
M-07-56	X14068	126	128	0.86	0.17	101	2.8	205	148	65	207	AS7-5743a
M-07-56	X14069	128	130	0.63	0.16	160	2.2	40	158	10	302	AS7-5743a
M-07-56	X14070	130	132	0.86	0.16	64	2.2	10	92	0.1	317	AS7-5743a
M-07-56	X14071	132	134	0.84	0.17	79	1.8	10	68	0.1	145	AS7-5738a
M-07-56	X14072	134	136	0.79	0.15	56	1.5	0.1	90	0.1	193	AS7-5738a
M-07-56	X14073	136	138	0.77	0.16	50	1.9	10	56	0.1	177	AS7-5738a
M-07-56	X14074	138	140	0.77	0.12	135	1.6	5	128	0.1	259	AS7-5738a
M-07-56	X14075	140	142	0.80	0.16	54	1.3	10	86	0.1	300	AS7-5738a
M-07-56	X14076	142	144	1.69	0.24	67	1.7	5	46	0.1	147	AS7-5738a
M-07-56	X14077	144	146	1.32	0.19	83	1.1	0.1	60	0.1	186	AS7-5738a
M-07-56	X14078	146	148	1.43	0.23	71	1.7	15	46	0.1	149	AS7-5738a
M-07-56	X14079	148	150	0.89	0.14	62	1.4	25	30	0.1	125	AS7-5738a
M-07-56	X14080	150	152	1.08	0.09	68	1.3	25	28	0.1	103	AS7-5738a
M-07-56	X14081	152	154	1.33	0.19	61	1.9	0.1	38	0.1	146	AS7-5738a
M-07-56	X14082	154	156	0.67	0.18	50	2.1	0.1	118	0.1	212	AS7-5738a
M-07-56	X14083	156	158	1.79	0.12	79	1.5	10	106	0.1	285	AS7-5738a
M-07-56	X14084	158	160	0.89	0.21	47	2	5	76	0.1	299	AS7-5738a
M-07-56	X14085	160	162	0.53	0.20	93	1.6	0.1	200	0.1	250	AS7-5738a
M-07-56	X14086	162	164	0.93	0.23	71	2	0.1	126	0.1	330	AS7-5738a
M-07-56	X14087	164	166	0.53	0.31	61	1.8	0.1	124	0.1	167	AS7-5738a
M-07-56	X14088	166	168.8	1.48	0.23	84	2.1	0.1	44	0.1	134	AS7-5738a
M-07-56	X14089	168.8	171.3	0.57	0.22	62	5.5	10	120	0.1	269	AS7-5738a
M-07-56	X14090	171.3	173.13	0.64	0.20	81	1.7	0.1	62	0.1	135	AS7-5738a
M-07-56	X14091	173.13	176	1.52	0.23	123	1.8	0.1	52	0.1	168	AS7-5738a
M-07-56	X14092	176	178	1.08	0.25	85	1.3	10	42	0.1	121	AS7-5738a
M-07-56	X14094	178	180	0.90	0.23	49	1.6	20	52	0.1	116	AS7-5738a
M-07-56	X14095	180	182	1.74	0.28	70	2.1	0.1	162	0.1	962	AS7-5738a
M-07-56	X14096	182	183.8	1.01	0.22	102	1.9	10	448	0.1	1295	AS7-5738a
M-07-56	X14097	183.8	185.5	0.56	0.12	72	1	10	90	0.1	115	AS7-5738a
M-07-56	X14098	185.5	186.7	1.08	0.21	75	1.8	15	110	0.1	139	AS7-5738a
M-07-56	X14099	186.7	188.5	0.49	0.08	36	1	15	108	0.1	576	AS7-5738a
M-07-56	X14100	188.5	190.2	1.23	0.20	89	1.7	15	72	0.1	108	AS7-5738a
M-07-56	X14101	190.2	192	1.28	0.23	74	1.8	10	38	0.1	34	AS7-5738a
M-07-56	X14102	192	193.55	0.86	0.20	134	1.3	15	28	0.1	22	AS7-5738a
M-07-56	X14103	193.55	195.7	0.90	0.19	434	2.8	90	102	5	92	AS7-5738a
M-07-56	X14106	195.7	197.9	0.92	0.11	56	1.9	35	84	10	133	AS7-5713ar
M-07-56	X14107	197.9	200	0.64	0.16	60	1.3	15	90	0.1	173	AS7-5713ar
M-07-56	X14108	200	202	1.14	0.16	72	1.4	5	32	0.1	52	AS7-5713ar
M-07-56	X14109	202	204	1.34	0.23	91	2.5	10	14	0.1	37	AS7-5713ar
M-07-56	X14110	204	206	0.80	0.10	51	1.4	5	64	0.1	79	AS7-5713ar
M-07-56	X14111	206	208	0.22	0.11	70	2	25	82	0.1	94	AS7-5713ar
M-07-56	X14112	208	210	1.46	0.25	202	3.2	45	44	10	35	AS7-5713ar
M-07-56	X14113	210	212	0.73	0.17	71	2.3	25	40	5	34	AS7-5713ar
M-07-56	X14114	212	214	1.63	0.25	62	3.2	15	24	0.1	38	AS7-5713ar
M-07-56	X14115	214	216	1.98	0.27	52	3.7	105	44	25	73	AS7-5713ar
M-07-56	X14116	216	218	0.73	0.18	70	2.7	200	66	45	91	AS7-5713ar
M-07-56	X14117	218	220	0.75	0.18	89	3.2	20	20	0.1	17	AS7-5713ar
M-07-56	X14118	220	222	1.17	0.20	59	2.7	10	24	0.1	39	AS7-5713ar
M-07-56	X14119	222	224	0.97	0.19	77	2.5	15	14	0.1	44	AS7-5713ar
M-07-56	X14120	224	226	1.01	0.23	62	2.6	10	34	0.1	79	AS7-5713ar
M-07-56	X14121	226	228	1.00	0.17	139	2.3	10	24	0.1	41	AS7-5713ar
M-07-56	X14122	228	230	1.04	0.22	65	2.6	15	16	0.1	84	AS7-5713ar
M-07-56	X14123	230	232	1.14	0.15	74	2.3	15	22	0.1	35	AS7-5713ar
M-07-56	X14124	232	234	1.06	0.18	101	2.1	10	26	0.1	47	AS7-5713ar
M-07-56	X14125	234	236	0.65	0.12	102	2	20	42	0.1	67	AS7-5713ar
M-07-56	X14126	236	238	1.00	0.14	58	2.2	15	18	0.1	43	AS7-5713ar
M-07-56	X14127	238	240	0.88	0.13	48	1.7	10	24	0.1	35	AS7-5713ar
M-07-56	X14128	240	242	0.44	0.15	79	1.2	5	36	0.1	41	AS7-5713ar
M-07-56	X14129	242	244	0.56	0.16	49	1.1	10	30	0.1	30	AS7-5713ar
M-07-56	X14130	244	246	0.38	0.18	66	1.2	10	30	0.1	73	AS7-5713ar
M-07-56	X14131	246	248.03	0.47	0.15	53	1.7	10	38	0.1	91	AS7-5713ar

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-56	X14132	248.03	250	0.30	0.10	62	2.1	15	1016	0.1	207	AS7-5713ar
M-07-56	X14133	250	251.95	0.72	0.13	57	2.6	20	116	0.1	220	AS7-5713ar
M-07-56	X14134	251.95	254	0.63	0.07	86	1.9	40	16	0.1	219	AS7-5713ar
M-07-56	X14135	254	256	0.61	0.11	72	2.3	40	24	0.1	268	AS7-5713ar
M-07-56	X14136	256	257.5	0.69	0.14	79	3.1	45	20	0.1	67	AS7-5713ar
M-07-56	X14137	257.5	260	0.13	0.04	18	1.1	80	14	0.1	241	AS7-5713ar
M-07-56	X14138	260	262	0.00	0.00	0.1	0.01	80	16	0.1	230	AS7-5713ar
M-07-56	X14141	262	264.5	0.00	0.00	0.1	0.01	85	22	0.1	203	AS7-5703a
M-07-56	X14142	264.5	266.95	0.07	0.02	14	0.3	50	18	0.1	282	AS7-5703a
M-07-56	X14143	266.95	269	0.37	0.07	66	1.4	60	30	0.1	136	AS7-5703a
M-07-56	X14144	269	271	0.51	0.13	66	2.5	115	82	10	141	AS7-5703a
M-07-56	X14145	271	273	0.49	0.14	50	1.2	30	50	0.1	130	AS7-5703a
M-07-56	X14146	273	275	0.81	0.12	65	0.7	35	28	0.1	102	AS7-5703a
M-07-56	X14147	275	277	0.61	0.13	82	1	85	24	0.1	121	AS7-5703a
M-07-56	X14148	277	279	0.56	0.10	337	0.6	25	18	0.1	80	AS7-5703a
M-07-56	X14149	279	281	0.40	0.09	77	0.7	45	36	0.1	78	AS7-5703a
M-07-56	X14150	281	283	0.31	0.07	43	0.6	25	34	0.1	63	AS7-5703a
M-07-56	X14151	283	285	0.41	0.12	74	1	25	34	0.1	64	AS7-5703a
M-07-56	X14152	285	287	0.31	0.09	99	0.6	25	30	0.1	44	AS7-5703a
M-07-56	X14153	287	289	0.60	0.09	55	1.2	30	22	0.1	72	AS7-5703a
M-07-56	X14154	289	291	0.86	0.20	60	2	25	58	0.1	69	AS7-5703a
M-07-56	X14155	291	293	0.65	0.15	93	1.3	20	30	0.1	58	AS7-5703a
M-07-56	X14156	293	295	0.64	0.12	80	1.5	15	40	0.1	47	AS7-5703a
M-07-56	X14157	295	297	0.68	0.19	72	1.8	20	32	0.1	55	AS7-5703a
M-07-56	X14158	297	299	0.56	0.13	60	1.2	15	34	0.1	37	AS7-5703a
M-07-56	X14159	299	301	1.36	0.18	57	7.4	205	36	30	104	AS7-5703a
M-07-56	X14160	301	303	0.78	0.12	36	2.3	45	30	10	85	AS7-5703a
M-07-56	X14161	303	305	0.45	0.14	56	1.7	15	24	0.1	68	AS7-5703a
M-07-56	X14162	305	307	0.39	0.10	101	1.5	30	16	0.1	101	AS7-5703a
M-07-56	X14163	307	309	0.35	0.10	191	1	20	22	0.1	95	AS7-5703a
M-07-56	X14164	309	311	0.43	0.08	146	1	25	46	0.1	137	AS7-5703a
M-07-56	X14166	311	313	0.34	0.09	56	1	15	74	0.1	60	AS7-5703a
M-07-56	X14167	313	315	0.31	0.07	80	0.6	20	60	0.1	121	AS7-5703a
M-07-56	X14168	315	317	0.48	0.08	153	0.8	20	46	0.1	80	AS7-5703a
M-07-56	X14169	317	319	0.43	0.09	109	0.6	20	38	0.1	69	AS7-5703a
M-07-56	X14171	319	321	0.45	0.08	82	0.4	20	20	0.1	42	AS7-5703a
M-07-56	X14172	321	323	0.34	0.07	171	0.01	20	30	0.1	73	AS7-5703a
M-07-56	X14173	323	325	0.33	0.06	55	0.5	20	14	0.1	50	AS7-5703a
M-07-56	X14174	325	327	0.55	0.10	83	0.7	20	22	0.1	63	AS7-5703a
M-07-56	X14175	327	329	0.47	0.06	131	0.6	15	30	0.1	37	AS7-5703a
M-07-56	X14176	329	331	0.32	0.09	63	0.7	20	20	0.1	51	AS7-5711a
M-07-56	X14177	331	332.8	0.26	0.08	101	0.7	45	4	0.1	45	AS7-5711a
M-07-56	X14178	332.8	335	0.00	0.01	0.1	0.01	45	4	0.1	62	AS7-5711a
M-07-56	X14179	335	337.2	0.00	0.01	0.1	0.01	50	10	0.1	93	AS7-5711a
M-07-56	X14180	337.2	339	0.23	0.08	95	0.7	30	14	0.1	53	AS7-5711a
M-07-56	X14181	339	341.25	0.17	0.07	116	0.7	25	30	0.1	83	AS7-5711a
M-07-56	X14182	341.25	344	0.00	0.00	7	0.01	55	4	0.1	107	AS7-5711a
M-07-56	X14183	344	346	0.20	0.05	56	0.3	35	6	0.1	88	AS7-5711a
M-07-56	X14184	346	348	0.25	0.07	31	0.4	25	22	0.1	72	AS7-5711a
M-07-56	X14185	348	350	0.27	0.07	87	0.5	20	30	0.1	67	AS7-5711a
M-07-56	X14186	350	352	0.38	0.08	66	0.7	30	30	5	89	AS7-5711a
M-07-56	X14187	352	354	0.35	0.07	78	0.4	20	26	0.1	55	AS7-5711a
M-07-56	X14188	354	356	0.16	0.06	28	0.5	30	16	5	38	AS7-5711a
M-07-56	X14189	356	358	0.29	0.07	29	0.6	20	14	0.1	29	AS7-5711a
M-07-56	X14190	358	360	0.40	0.06	62	3.4	50	18	15	47	AS7-5711a
M-07-56	X14191	360	362	0.43	0.07	19	9.4	70	18	35	56	AS7-5711a
M-07-56	X14192	362	364	0.27	0.06	33	2	35	26	0.1	75	AS7-5711a
M-07-56	X14193	364	366	0.39	0.06	43	2.3	40	20	10	74	AS7-5711a
M-07-56	X14194	366	368	0.28	0.05	141	1.2	20	12	0.1	42	AS7-5711a
M-07-56	X14195	368	370	0.12	0.03	46	0.6	15	26	0.1	18	AS7-5711a
M-07-56	X14196	370	372	0.41	0.06	37	1.1	30	10	0.1	25	AS7-5711a
M-07-56	X14197	372	374	0.33	0.05	104	0.8	25	22	0.1	41	AS7-5711a
M-07-56	X14198	374	376	0.25	0.06	50	0.6	20	16	0.1	31	AS7-5711a
M-07-56	X14199	376	378	0.16	0.04	117	0.7	25	30	10	22	AS7-5711a
M-07-56	X14201	378	380	0.21	0.06	77	0.4	15	14	0.1	39	AS7-5711a
M-07-56	X14203	380	382	0.18	0.05	158	0.6	15	16	0.1	37	AS7-5711a
M-07-56	X14204	382	384	0.22	0.07	46	1.1	40	18	20	34	AS7-5711a
M-07-56	X14205	384	386	0.23	0.06	48	4.2	70	58	35	76	AS7-5711a
M-07-56	X14207	386	388	0.29	0.04	28	1.9	25	26	5	38	AS7-5711a
M-07-56	X14208	388	390	0.77	0.04	29	8.7	45	36	25	52	AS7-5711a
M-07-56	X14209	390	392	0.74	0.04	93	12.8	50	54	40	47	AS7-5711a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-56	X14210	392	394	0.46	0.06	26	3.5	30	6	0.1	43	AS7-5711a
M-07-56	X14211	394	396	0.65	0.05	122	4	5	36	10	41	AS7-5735a
M-07-56	X14212	396	398	0.22	0.04	87	2.4	0.1	30	0.1	29	AS7-5735a
M-07-56	X14213	398	400	0.18	0.05	61	2.7	0.1	32	0.1	15	AS7-5735a
M-07-56	X14214	400	402	0.29	0.04	94	3	0.1	48	10	23	AS7-5735a
M-07-56	X14215	402	404	1.25	0.07	40	8.5	10	26	15	46	AS7-5735a
M-07-56	X14216	404	406	0.36	0.06	27	2.4	0.1	28	0.1	34	AS7-5735a
M-07-56	X14217	406	408	0.21	0.04	14	1.7	0.1	30	10	44	AS7-5735a
M-07-56	X14218	408	410	0.23	0.05	74	1.3	0.1	32	10	47	AS7-5735a
M-07-56	X14219	410	412	0.25	0.04	65	1.5	0.1	32	5	29	AS7-5735a
M-07-56	X14220	412	414	0.24	0.04	25	0.8	0.1	30	0.1	23	AS7-5735a
M-07-56	X14221	414	416	0.23	0.04	43	0.4	0.1	34	15	24	AS7-5735a
M-07-56	X14222	416	418	0.10	0.02	28	0.6	0.1	20	0.1	8	AS7-5735a
M-07-56	X14223	418	420	0.20	0.03	28	0.6	0.1	24	0.1	16	AS7-5735a
M-07-56	X14224	420	422	0.23	0.02	28	0.7	0.1	28	0.1	11	AS7-5735a
M-07-56	X14225	422	424	0.15	0.02	51	0.6	0.1	38	10	23	AS7-5735a
M-07-56	X14226	424	426	0.10	0.02	125	1	0.1	26	10	14	AS7-5735a
M-07-56	X14227	426	428.25	0.23	0.02	67	0.2	0.1	30	10	19	AS7-5735a
M-07-57	X05802	3.05	5	0.57	0.13	43	1.3	5	40	15	100	AS7-5710a
M-07-57	X05803	5	7	0.61	0.19	31	1.9	5	44	10	100	AS7-5710a
M-07-57	X05804	7	9	0.98	0.22	38	2.5	0.1	50	10	92	AS7-5710a
M-07-57	X05805	9	11	0.82	0.21	34	2.4	10	46	0.1	93	AS7-5710a
M-07-57	X05806	11	13	0.46	0.13	52	1.7	10	48	25	187	AS7-5710a
M-07-57	X05807	13	15	0.51	0.17	39	2.7	25	80	15	1676	AS7-5710a
M-07-57	X05809	15	17	0.62	0.13	35	2.5	15	124	15	433	AS7-5710a
M-07-57	X05810	17	19	0.61	0.15	30	1.8	10	44	10	112	AS7-5710a
M-07-57	X05811	19	21	0.51	0.13	34	1.6	15	42	10	86	AS7-5710a
M-07-57	X05812	21	23	0.50	0.13	35	1.6	15	38	0.1	81	AS7-5710a
M-07-57	X05813	23	25	0.58	0.16	37	2	15	40	10	79	AS7-5710a
M-07-57	X05814	25	27	0.44	0.13	52	1.9	20	68	15	227	AS7-5710a
M-07-57	X05815	27	29	0.49	0.17	32	2.2	25	44	5	78	AS7-5710a
M-07-57	X05816	29	31	0.48	0.12	30	1.4	10	36	0.1	72	AS7-5710a
M-07-57	X05817	31	33	0.66	0.16	34	1.8	5	42	5	92	AS7-5710a
M-07-57	X05819	33	35	0.79	0.29	68	2.4	25	42	20	70	AS7-5710a
M-07-57	X05820	35	37	0.62	0.16	40	2.1	10	58	15	86	AS7-5710a
M-07-57	X05821	37	39	0.28	0.08	23	0.9	15	50	10	90	AS7-5710a
M-07-57	X05822	39	41	0.76	0.17	41	1.5	0.1	42	40	72	AS7-5710a
M-07-57	X05824	41	43	0.74	0.30	46	2.6	15	44	10	71	AS7-5710a
M-07-57	X05825	43	45	0.51	0.18	47	2.1	15	32	10	50	AS7-5710a
M-07-57	X05826	45	47	0.35	0.11	40	1.5	30	38	5	57	AS7-5710a
M-07-57	X05827	47	49	0.40	0.13	35	1.9	20	62	10	91	AS7-5710a
M-07-57	X05828	49	51	0.65	0.17	78	1.9	15	42	15	55	AS7-5710a
M-07-57	X05829	51	53	0.35	0.11	103	1.1	20	48	15	56	AS7-5710a
M-07-57	X05830	53	55.15	0.32	0.09	37	1	10	32	20	58	AS7-5710a
M-07-57	X05831	57.2	59	0.46	0.11	31	1.5	0.1	40	15	70	AS7-5710a
M-07-57	X05832	59	60.5	0.51	0.15	34	1.9	20	38	10	66	AS7-5710a
M-07-57	X05833	61.2	63	0.51	0.18	29	2.2	15	16	0.1	122	AS7-5712a
M-07-57	X05834	63	65	0.53	0.15	28	7.4	60	28	0.1	139	AS7-5712a
M-07-57	X05835	65	67	0.43	0.17	28	2.7	15	18	0.1	136	AS7-5712a
M-07-57	X05836	67	69	0.31	0.11	26	1.3	15	14	0.1	109	AS7-5712a
M-07-57	X05837	69	71	0.36	0.13	22	2.7	20	60	0.1	139	AS7-5712a
M-07-57	X05838	71	73	0.35	0.15	24	1.8	20	48	0.1	185	AS7-5712a
M-07-57	X05839	73	74.4	0.27	0.11	26	1.4	15	6	0.1	141	AS7-5712a
M-07-57	X05840	74.4	77.72	0.26	0.11	33	1.4	15	8	0.1	129	AS7-5712a
M-07-57	X05841	77.72	80.77	0.38	0.13	31	1.9	15	8	0.1	138	AS7-5712a
M-07-57	X05842	80.77	82.25	0.34	0.14	52	1.7	15	8	0.1	131	AS7-5712a
M-07-57	X05843	82.25	83.82	0.41	0.14	25	2.1	15	14	0.1	139	AS7-5712a
M-07-57	X05844	83.82	86.86	0.28	0.11	19	1.6	10	4	0.1	116	AS7-5712a
M-07-57	X05845	86.86	88.5	0.25	0.11	21	1.3	15	10	0.1	109	AS7-5712a
M-07-57	X05846	88.5	90	0.55	0.14	27	1.7	10	8	0.1	94	AS7-5712a
M-07-57	X05847	90	92	0.77	0.21	20	3.2	20	32	0.1	100	AS7-5712a
M-07-57	X05848	92	94	0.73	0.21	18	2.6	20	12	0.1	114	AS7-5712a
M-07-57	X05849	94	96	0.70	0.17	18	1.8	15	10	0.1	105	AS7-5712a
M-07-57	X05850	96	98	0.50	0.17	35	2.1	15	10	0.1	114	AS7-5712a
M-07-57	X05851	98	100	0.38	0.12	35	1.4	15	8	0.1	119	AS7-5712a
M-07-57	X05852	100	102	0.72	0.20	25	2.6	15	12	0.1	88	AS7-5712a
M-07-57	X05853	102	104	0.51	0.14	20	1.8	15	10	0.1	80	AS7-5712a
M-07-57	X05854	104	106	0.34	0.14	24	1.7	15	6	0.1	97	AS7-5712a
M-07-57	X05855	106	108	0.33	0.11	17	1.2	10	2	0.1	88	AS7-5712a
M-07-57	X05856	108	109	0.36	0.12	22	1.5	10	6	0.1	77	AS7-5712a
M-07-57	X05859	109	111	0.43	0.14	17	2.3	20	8	0.1	73	AS7-5712a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-57	X05860	111	113	0.64	0.21	18	3.3	10	10	0.1	60	AS7-5712a
M-07-57	X05861	113	115	1.09	0.33	16	14.5	20	46	0.1	80	AS7-5712a
M-07-57	X05862	115	117	0.62	0.20	15	2.3	10	12	0.1	73	AS7-5712a
M-07-57	X05863	117	119	0.37	0.11	35	1.4	10	8	0.1	54	AS7-5712a
M-07-57	X05864	119	121	0.55	0.16	16	2	10	12	0.1	48	AS7-5712a
M-07-57	X05865	121	123	0.56	0.17	17	1.9	10	8	0.1	58	AS7-5712a
M-07-57	X05866	123	125	0.77	0.21	23	2.6	10	12	0.1	48	AS7-5712a
M-07-57	X05867	125	127	0.72	0.16	43	2.1	10	8	0.1	49	AS7-5712a
M-07-57	X05868	127	129	0.49	0.14	46	1.6	20	22	0.1	63	AS7-5699a
M-07-57	X05869	129	131	1.87	0.15	19	2.4	115	26	5	65	AS7-5699a
M-07-57	X05870	131	133	1.62	0.15	19	1.8	60	14	0.1	78	AS7-5699a
M-07-57	X05871	133	135	0.49	0.15	19	1.8	25	16	0.1	72	AS7-5699a
M-07-57	X05873	135	137	0.78	0.21	29	2.6	15	16	0.1	76	AS7-5699a
M-07-57	X05874	137	139	1.53	0.48	19	4.5	15	22	0.1	87	AS7-5699a
M-07-57	X05875	139	141	0.79	0.26	19	2.6	15	36	0.1	191	AS7-5699a
M-07-57	X05876	141	143	0.53	0.18	25	2	15	16	0.1	67	AS7-5699a
M-07-57	X05878	143	145	0.59	0.14	17	1.8	15	18	0.1	80	AS7-5699a
M-07-57	X05879	145	147	0.43	0.12	18	1.6	20	16	0.1	102	AS7-5699a
M-07-57	X05880	147	149	0.63	0.17	18	1.7	20	14	0.1	100	AS7-5699a
M-07-57	X05881	149	151	0.70	0.17	22	2.3	20	22	0.1	79	AS7-5699a
M-07-57	X05882	151	153	0.50	0.18	13	3.8	25	334	0.1	1263	AS7-5699a
M-07-57	X05883	153	155	0.38	0.13	18	1.6	15	12	0.1	57	AS7-5699a
M-07-57	X05884	155	157	0.48	0.13	15	1.5	25	18	0.1	80	AS7-5699a
M-07-57	X05885	157	159	0.43	0.11	16	1.2	20	16	0.1	85	AS7-5699a
M-07-57	X05887	159	161	0.57	0.16	22	1.6	15	10	0.1	83	AS7-5699a
M-07-57	X05888	161	163	0.51	0.15	21	1.3	15	12	0.1	85	AS7-5699a
M-07-57	X05889	163	165	0.73	0.18	13	1.6	20	12	0.1	69	AS7-5699a
M-07-57	X05890	165	167	0.63	0.18	12	1.8	15	10	0.1	73	AS7-5699a
M-07-57	X05891	167	169	0.62	0.19	16	1.9	15	10	0.1	74	AS7-5699a
M-07-57	X05892	169	171	1.03	0.27	13	2.6	20	10	0.1	86	AS7-5699a
M-07-57	X05893	171	173	0.28	0.06	8	0.6	20	6	0.1	104	AS7-5699a
M-07-57	X05894	173	175	0.43	0.10	21	1.6	50	14	0.1	121	AS7-5699a
M-07-57	X05895	175	177	0.49	0.10	14	1.5	45	12	5	119	AS7-5699a
M-07-57	X05896	177	179	0.46	0.12	17	1.5	25	12	0.1	75	AS7-5699a
M-07-57	X05897	179	181	0.46	0.13	17	1.4	20	8	0.1	72	AS7-5699a
M-07-57	X05898	181	183	0.47	0.09	19	1.4	30	8	0.1	67	AS7-5699a
M-07-57	X05899	183	185	0.57	0.12	13	1.6	40	14	0.1	73	AS7-5699a
M-07-57	X05900	185	187	0.51	0.14	21	1.3	20	6	0.1	96	AS7-5699a
M-07-57	X05901	187	189	0.34	0.12	18	1.4	20	6	0.1	86	AS7-5699a
M-07-57	X05902	189	191	0.35	0.13	21	1.3	20	8	0.1	83	AS7-5699a
M-07-57	X05903	191	193	0.34	0.11	27	1.1	0.1	32	5	69	AS7-5700a
M-07-57	X05904	193	195	0.26	0.10	22	1.1	0.1	28	15	69	AS7-5700a
M-07-57	X05905	195	197	0.39	0.12	25	1.1	0.1	30	15	68	AS7-5700a
M-07-57	X05906	197	199	0.43	0.16	27	1.8	0.1	30	30	56	AS7-5700a
M-07-57	X05908	199	201	0.46	0.13	26	1.8	15	38	15	77	AS7-5700a
M-07-57	X05909	201	203	0.41	0.13	28	1.8	15	28	15	67	AS7-5700a
M-07-57	X05910	203	205	0.43	0.13	28	1.5	5	28	15	63	AS7-5700a
M-07-57	X05911	205	207	0.44	0.13	23	1.3	15	40	20	91	AS7-5700a
M-07-57	X05912	207	209	0.43	0.14	19	1.8	5	40	15	78	AS7-5700a
M-07-57	X05913	209	211	0.44	0.12	26	1.7	10	40	20	97	AS7-5700a
M-07-57	X05915	211	213	0.48	0.10	20	1.4	20	38	15	69	AS7-5700a
M-07-57	X05916	213	215	0.32	0.11	18	1.4	5	36	15	90	AS7-5700a
M-07-57	X05917	215	217	0.81	0.14	21	2.6	35	46	10	78	AS7-5700a
M-07-57	X05918	217	219	0.46	0.12	30	2	15	46	15	87	AS7-5700a
M-07-57	X05919	219	221	2.77	0.11	22	2.6	10	40	15	77	AS7-5700a
M-07-57	X05920	221	223	0.54	0.16	23	1.8	15	48	25	80	AS7-5700a
M-07-57	X05921	223	225	0.46	0.14	24	1.3	10	42	15	73	AS7-5700a
M-07-57	X05922	225	227	0.46	0.13	21	1.3	0.1	42	15	79	AS7-5700a
M-07-57	X05923	227	229	0.44	0.16	27	1.9	5	40	15	81	AS7-5700a
M-07-57	X05924	229	231	0.43	0.12	22	1.7	15	38	15	81	AS7-5700a
M-07-57	X05925	231	233	0.46	0.14	27	1.7	0.1	36	15	75	AS7-5700a
M-07-57	X05926	233	235	0.41	0.14	22	1.5	0.1	32	10	76	AS7-5700a
M-07-57	X05927	235	237	0.81	0.15	25	1.6	0.1	38	20	79	AS7-5700a
M-07-57	X05928	237	239	0.59	0.18	20	1.8	0.1	30	20	81	AS7-5700a
M-07-57	X05930	239	241	0.53	0.16	20	1.7	0.1	28	10	95	AS7-5700a
M-07-57	X05931	241	243	0.45	0.12	26	1	0.1	26	30	76	AS7-5700a
M-07-57	X05932	243	245	0.29	0.10	22	0.9	0.1	28	5	74	AS7-5700a
M-07-57	X05933	245	247	0.56	0.18	20	2.3	0.1	38	10	91	AS7-5700a
M-07-57	X05934	247	249	0.33	0.12	33	1.5	0.1	38	15	79	AS7-5700a
M-07-57	X05935	249	250.75	0.33	0.14	34	1.1	0.1	34	0.1	90	AS7-5700a
M-07-57	X05936	250.75	253	0.00	0.00	9	0.01	0.1	58	25	90	AS7-5700a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-57	X05937	253	255	0.03	0.00	10	0.01	5	70	35	92	AS7-5700a
M-07-57	X05938	255	257.2	0.00	0.00	15	0.01	10	88	50	113	AS7-5708a
M-07-57	X05939	257.2	259	0.97	0.23	23	2.9	0.1	48	20	94	AS7-5708a
M-07-57	X05940	259	261	0.58	0.17	22	1.8	0.1	38	20	83	AS7-5708a
M-07-57	X05941	261	263	0.31	0.11	21	0.9	0.1	36	20	81	AS7-5708a
M-07-57	X05942	263	265	0.40	0.14	27	1.7	0.1	36	15	80	AS7-5708a
M-07-57	X05943	265	267	0.34	0.16	31	1.5	0.1	38	15	83	AS7-5708a
M-07-57	X05944	267	269	0.51	0.18	20	2.5	0.1	34	15	76	AS7-5708a
M-07-57	X05945	269	271	0.32	0.14	27	2.4	0.1	48	35	91	AS7-5708a
M-07-57	X05946	271	273	0.42	0.14	19	2	0.1	44	0.1	86	AS7-5708a
M-07-57	X05947	273	275	0.34	0.14	27	2	5	70	15	96	AS7-5708a
M-07-57	X05948	275	276.35	0.28	0.11	33	2.8	0.1	54	25	130	AS7-5708a
M-07-57	X05949	276.35	278	0.45	0.13	30	4.8	30	66	15	118	AS7-5708a
M-07-57	X05950	278	280	0.44	0.13	29	3.8	20	60	15	120	AS7-5708a
M-07-57	X05951	280	282	0.42	0.12	27	2.6	15	54	20	96	AS7-5708a
M-07-57	X05952	282	284	1.42	0.13	41	6.2	40	74	35	106	AS7-5708a
M-07-57	X05954	284	286	0.59	0.17	29	4.6	65	44	10	99	AS7-5708a
M-07-57	X05955	286	288	0.40	0.15	30	2.6	35	50	10	105	AS7-5708a
M-07-57	X05956	288	290	0.35	0.13	21	1.8	10	32	10	75	AS7-5708a
M-07-57	X05957	290	292	0.31	0.10	14	1.7	15	38	20	75	AS7-5708a
M-07-57	X05958	292	294	0.35	0.15	17	2.3	0.1	26	10	62	AS7-5708a
M-07-57	X05959	294	296	0.44	0.16	13	4.1	0.1	64	10	186	AS7-5708a
M-07-57	X05960	296	298	0.28	0.14	14	1.4	10	36	10	68	AS7-5708a
M-07-57	X05961	298	300	0.27	0.14	13	1.4	0.1	36	10	75	AS7-5708a
M-07-57	X05962	300	302	0.48	0.25	14	2.7	5	44	10	79	AS7-5708a
M-07-57	X05963	302	304	0.64	0.19	14	2.1	5	42	15	83	AS7-5708a
M-07-57	X05964	304	306	0.38	0.15	13	2	10	36	15	76	AS7-5708a
M-07-57	X05966	306	308	0.31	0.12	12	2.1	20	50	20	71	AS7-5708a
M-07-57	X05967	308	310	0.24	0.10	12	1.7	0.1	36	15	66	AS7-5708a
M-07-57	X05968	310	312	0.23	0.10	13	1.3	15	38	15	69	AS7-5708a
M-07-57	X05969	312	314	0.17	0.07	15	1	10	34	10	73	AS7-5708a
M-07-57	X05970	314	316	0.27	0.11	20	1.4	0.1	42	25	85	AS7-5708a
M-07-57	X05971	316	318	0.30	0.12	21	1.7	5	32	5	54	AS7-5708a
M-07-57	X05972	318	320	0.25	0.09	12	1.6	20	56	0.1	92	AS7-5708a
M-07-57	X05973	320	322	0.32	0.11	17	1.8	50	20	0.1	77	AS7-5740a
M-07-57	X05974	322	324	0.57	0.31	14	3.2	30	16	0.1	40	AS7-5740a
M-07-57	X05976	324	326	0.53	0.17	10	2	30	14	0.1	62	AS7-5740a
M-07-57	X05977	326	328	0.39	0.16	9	1.8	25	8	0.1	65	AS7-5740a
M-07-57	X05978	328	330	0.73	0.31	19	3	30	8	0.1	66	AS7-5740a
M-07-57	X05979	330	332	1.35	0.38	12	4	15	10	0.1	76	AS7-5740a
M-07-57	X05981	332	334	0.78	0.29	21	2.6	15	12	0.1	75	AS7-5740a
M-07-57	X05982	334	336	0.46	0.22	24	2.1	20	8	0.1	102	AS7-5740a
M-07-57	X05983	336	338	0.56	0.22	25	1.8	15	6	0.1	76	AS7-5740a
M-07-57	X05984	338	340	0.50	0.20	24	2	25	16	0.1	75	AS7-5740a
M-07-57	X05985	340	342	0.51	0.20	30	2	20	12	0.1	64	AS7-5740a
M-07-57	X05986	342	344	0.47	0.18	28	2.1	15	8	0.1	69	AS7-5740a
M-07-57	X05987	344	346	0.55	0.21	22	2.4	15	8	0.1	56	AS7-5740a
M-07-57	X05988	346	348	0.65	0.27	21	3	15	4	0.1	76	AS7-5740a
M-07-57	X05989	348	350	0.33	0.18	28	2.1	15	6	0.1	76	AS7-5740a
M-07-57	X05990	350	352	0.31	0.15	28	1.7	15	6	0.1	71	AS7-5740a
M-07-57	X05991	352	354	0.60	0.24	18	2.8	20	16	0.1	94	AS7-5740a
M-07-57	X05992	354	356	0.21	0.11	30	1.4	15	8	0.1	77	AS7-5740a
M-07-57	X05993	356	358	0.35	0.15	49	2.6	25	14	0.1	89	AS7-5740a
M-07-57	X05994	358	360	0.43	0.21	52	2.5	20	6	0.1	94	AS7-5740a
M-07-57	X05995	360	361.5	0.29	0.12	44	1.4	15	10	0.1	87	AS7-5740a
M-07-57	X05996	361.5	363	0.28	0.13	85	1.5	15	10	0.1	94	AS7-5740a
M-07-57	X05997	363	365	0.28	0.15	47	1.4	15	8	0.1	103	AS7-5740a
M-07-57	X05999	365	367	0.32	0.17	32	1.8	15	8	0.1	119	AS7-5740a
M-07-57	X06000	367	369	0.48	0.26	61	2.4	20	12	0.1	103	AS7-5740a
M-07-57	X06001	369	371	0.50	0.24	48	2.3	20	8	0.1	102	AS7-5740a
M-07-57	X06002	371	373	0.23	0.12	24	1.5	15	12	0.1	109	AS7-5740a
M-07-57	X06003	373	375	0.34	0.18	65	1.9	15	12	0.1	115	AS7-5740a
M-07-57	X06004	375	377	0.40	0.19	74	2	15	14	0.1	108	AS7-5740a
M-07-57	X06005	377	378.5	0.32	0.16	80	1.7	15	8	0.1	111	AS7-5740a
M-07-57	X06006	378.5	379.6	0.41	0.17	50	1.8	15	8	0.1	88	AS7-5740a
M-07-57	X06007	379.6	381	0.43	0.21	62	2.3	15	8	0.1	79	AS7-5740a
M-07-57	X06008	381	383	0.56	0.33	24	3.5	0.1	38	20	79	AS7-5724a
M-07-57	X06009	383	385	0.68	0.35	29	3.2	0.1	34	15	90	AS7-5724a
M-07-57	X06010	385	387	0.28	0.17	73	2	0.1	30	10	81	AS7-5724a
M-07-57	X06011	387	389	0.40	0.22	49	2.4	0.1	34	15	91	AS7-5724a
M-07-57	X06012	389	391	0.23	0.15	52	1.5	10	36	20	85	AS7-5724a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-57	X06014	391	393	0.34	0.18	44	2.2	0.1	36	15	82	AS7-5724a
M-07-57	X06015	393	395	0.41	0.20	29	2.2	5	30	10	81	AS7-5724a
M-07-57	X06016	395	397	0.21	0.12	29	1.3	5	30	10	70	AS7-5724a
M-07-57	X06017	397	399	0.30	0.14	66	1.8	0.1	32	10	66	AS7-5724a
M-07-57	X06018	399	401	0.39	0.18	42	2.3	15	34	30	89	AS7-5724a
M-07-57	X06019	401	403	0.26	0.15	28	1.7	0.1	30	10	69	AS7-5724a
M-07-57	X06020	403	405	0.39	0.17	18	2.1	10	30	10	75	AS7-5724a
M-07-57	X06021	405	406.1	0.19	0.09	19	1.1	10	24	15	56	AS7-5724a
M-07-57	X06022	406.1	408	0.31	0.14	24	1.4	5	28	5	66	AS7-5724a
M-07-57	X06023	408	410	0.35	0.19	39	1.7	15	32	15	98	AS7-5724a
M-07-57	X06024	410	412	0.37	0.19	34	1.8	5	32	10	83	AS7-5724a
M-07-57	X06025	412	414	0.52	0.27	21	2.4	10	36	10	68	AS7-5724a
M-07-57	X06026	414	416	0.28	0.13	38	1.6	0.1	28	10	66	AS7-5724a
M-07-57	X06027	416	418	0.46	0.20	40	7.2	5	522	10	959	AS7-5724a
M-07-57	X06029	418	420	0.44	0.17	44	2.3	0.1	30	25	78	AS7-5724a
M-07-57	X06030	420	422	0.25	0.13	27	1.9	10	30	15	79	AS7-5724a
M-07-57	X06031	422	424	0.37	0.17	22	1.8	10	26	15	73	AS7-5724a
M-07-57	X06032	424	425.18	0.72	0.36	37	3.9	10	28	0.1	48	AS7-5724a
M-07-58	X10446	4.5	6	0.86	0.15	43	2.5	30	62	5	117	AS7-5717a
M-07-58	X10447	6	8	0.81	0.18	45	2.7	30	56	10	131	AS7-5717a
M-07-58	X10448	8	10	0.94	0.23	41	3.4	10	98	30	119	AS7-5717a
M-07-58	X10449	10	12	0.73	0.24	32	3.4	15	46	10	86	AS7-5717a
M-07-58	X10450	12	14	1.47	0.36	24	4.8	5	50	5	62	AS7-5717a
M-07-58	X10451	14	16	0.98	0.19	21	2.6	10	48	10	82	AS7-5717a
M-07-58	X10452	16	18	0.69	0.21	25	2.9	0.1	48	10	72	AS7-5717a
M-07-58	X10453	18	20	0.80	0.10	14	1.6	15	28	0.1	56	AS7-5717a
M-07-58	X10454	20	22	1.01	0.38	26	4.8	0.1	62	0.1	43	AS7-5717a
M-07-58	X10455	22	24	0.77	0.28	22	4.2	5	88	10	76	AS7-5717a
M-07-58	X10456	24	26	0.85	0.18	37	2.7	10	70	25	133	AS7-5717a
M-07-58	X10458	26	28	0.89	0.15	43	2.5	10	42	10	88	AS7-5717a
M-07-58	X10460	28	30	0.82	0.22	28	3	5	42	0.1	66	AS7-5717a
M-07-58	X10461	30	32	0.80	0.19	30	2.8	10	46	0.1	62	AS7-5717a
M-07-58	X10462	32	34	0.66	0.17	37	2.2	0.1	36	10	64	AS7-5741a
M-07-58	X10463	34	36	0.59	0.23	24	4.7	0.1	210	10	887	AS7-5741a
M-07-58	X10464	36	38	0.81	0.21	26	3.2	0.1	82	10	137	AS7-5741a
M-07-58	X10465	38	40	0.61	0.18	43	2.2	5	64	15	117	AS7-5741a
M-07-58	X10466	40	42	1.11	0.31	24	4.2	5	66	10	71	AS7-5741a
M-07-58	X10467	42	44	0.62	0.18	23	2.5	0.1	44	15	78	AS7-5741a
M-07-58	X10468	44	46	0.84	0.17	28	2.9	0.1	42	10	74	AS7-5741a
M-07-58	X10469	46	48	0.62	0.14	23	2.2	0.1	40	5	59	AS7-5741a
M-07-58	X10470	48	50	0.80	0.18	34	2.3	0.1	36	10	64	AS7-5741a
M-07-58	X10471	50	52	1.03	0.28	23	3.1	0.1	42	10	58	AS7-5741a
M-07-58	X10472	52	54	1.13	0.25	26	3	0.1	42	20	61	AS7-5741a
M-07-58	X10473	54	56	0.93	0.18	22	2.2	0.1	42	15	150	AS7-5741a
M-07-58	X10474	56	58	0.53	0.24	16	3	0.1	46	0.1	26	AS7-5741a
M-07-58	X10475	58	60	0.78	0.23	21	2.8	0.1	56	10	111	AS7-5741a
M-07-58	X10476	60	62	0.51	0.32	14	4.1	0.1	40	5	64	AS7-5741a
M-07-58	X10477	62	64	0.50	0.27	15	2.7	10	48	0.1	113	AS7-5741a
M-07-58	X10478	64	66	1.01	0.28	17	3.1	0.1	40	0.1	115	AS7-5741a
M-07-58	X10479	66	68	1.22	0.37	16	3.3	0.1	32	10	44	AS7-5741a
M-07-58	X10480	68	70	1.62	0.44	11	3.7	0.1	28	0.1	45	AS7-5741a
M-07-58	X10482	70	72	1.44	0.22	17	1.9	0.1	24	0.1	66	AS7-5741a
M-07-58	X10483	72	74	0.40	0.22	20	2.7	0.1	118	30	97	AS7-5741a
M-07-58	X10484	74	75	0.81	0.30	23	2.4	0.1	60	5	48	AS7-5741a
M-07-58	X10485	75	77	1.68	0.33	16	3	0.1	44	0.1	53	AS7-5741a
M-07-58	X10486	77	79	0.84	0.20	25	2.4	0.1	42	0.1	68	AS7-5741a
M-07-58	X10487	79	81	0.87	0.37	21	4.3	0.1	92	0.1	100	AS7-5741a
M-07-58	X10488	81	83	1.45	0.31	18	2.8	0.1	42	10	96	AS7-5741a
M-07-58	X10489	83	85	1.72	0.33	34	3.3	10	60	20	107	AS7-5741a
M-07-58	X10491	85	87	1.05	0.26	28	2.4	0.1	48	10	76	AS7-5741a
M-07-58	X10492	87	89	1.08	0.55	13	4.9	0.1	52	5	37	AS7-5741a
M-07-58	X10493	89	91	0.35	0.29	13	3.5	0.1	84	10	92	AS7-5741a
M-07-58	X10494	91	93	0.45	0.31	15	2.8	0.1	44	20	82	AS7-5741a
M-07-58	X10495	93	95	0.51	0.21	21	2.5	0.1	44	0.1	186	AS7-5741a
M-07-58	X10496	95	97	0.72	0.18	16	3.2	0.1	108	5	168	AS7-5741a
M-07-58	X10497	97	99	0.92	0.21	11	2.2	15	34	0.1	151	AS7-5719a
M-07-58	X10498	99	101	0.93	0.20	16	2.5	15	26	0.1	119	AS7-5719a
M-07-58	X10499	101	103	0.73	0.20	14	2.1	10	36	0.1	99	AS7-5719a
M-07-58	X10501	103	105	0.73	0.19	21	2.2	15	34	0.1	125	AS7-5719a
M-07-58	X10502	105	107	0.65	0.20	17	2.1	15	20	0.1	111	AS7-5719a
M-07-58	X10504	107	109	1.03	0.21	14	2.4	10	28	0.1	86	AS7-5719a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-58	X10505	109	111	0.68	0.18	11	2.1	10	42	0.1	88	AS7-5719a
M-07-58	X10506	111	113	0.74	0.20	13	2.1	10	36	0.1	54	AS7-5719a
M-07-58	X10507	113	114.4	0.99	0.20	11	2.4	20	18	0.1	79	AS7-5719a
M-07-58	X10508	114.4	115.7	0.80	0.22	18	2.4	20	8	0.1	154	AS7-5719a
M-07-58	X10509	115.7	118	0.51	0.35	10	3.4	15	40	0.1	108	AS7-5719a
M-07-58	X10510	118	120	0.47	0.37	10	3.5	10	48	0.1	60	AS7-5719a
M-07-58	X10511	120	122	1.14	0.44	8	4.4	20	44	0.1	29	AS7-5719a
M-07-58	X10512	122	124	0.53	0.36	14	4.1	10	68	0.1	155	AS7-5719a
M-07-58	X10513	124	126	1.02	0.28	14	3.1	5	28	0.1	54	AS7-5719a
M-07-58	X10514	126	128	0.23	0.29	16	2.8	10	46	0.1	95	AS7-5719a
M-07-58	X10515	128	130	0.63	0.25	13	2.6	10	28	0.1	82	AS7-5719a
M-07-58	X10516	130	132	0.54	0.37	11	3.9	0.1	28	0.1	96	AS7-5719a
M-07-58	X10517	132	134	0.40	0.38	8	4.3	5	26	0.1	105	AS7-5719a
M-07-58	X10518	134	136	0.30	0.33	12	4.1	25	34	15	82	AS7-5719a
M-07-58	X10519	136	138	0.38	0.26	9	3.2	15	30	5	75	AS7-5719a
M-07-58	X10520	138	139.3	0.55	0.37	8	4.2	5	44	0.1	56	AS7-5719a
M-07-58	X10521	139.3	140.6	0.53	0.48	6	5.6	15	46	10	159	AS7-5719a
M-07-58	X10522	140.6	142	0.15	0.37	8	3.2	35	24	30	44	AS7-5719a
M-07-58	X10523	142	144	0.57	0.33	7	4.6	85	30	50	41	AS7-5719a
M-07-58	X10524	144	146	0.63	0.10	18	3.2	50	16	20	20	AS7-5719a
M-07-58	X10525	146	148	0.15	0.10	45	1.9	40	22	20	20	AS7-5719a
M-07-58	X10526	148	150	2.46	0.48	11	11.5	210	54	145	395	AS7-5719a
M-07-58	X10527	150	152	1.23	0.44	10	10.8	145	34	130	91	AS7-5719a
M-07-58	X10528	152	154	0.27	0.30	20	3.7	50	24	40	32	AS7-5719a
M-07-58	X10529	154	156	0.23	0.36	6	5.9	100	28	120	58	AS7-5719a
M-07-58	X10530	156	158	0.31	0.19	19	4.6	80	34	135	66	AS7-5719a
M-07-58	X10531	158	160	0.33	0.17	31	2.5	50	20	50	25	AS7-5719a
M-07-58	X10532	160	162	0.27	0.02	56	0.8	0.1	18	30	64	AS7-5715a
M-07-58	X10533	162	164	0.22	0.02	83	0.6	0.1	12	0.1	12	AS7-5715a
M-07-58	X10534	164	166	0.36	0.05	57	1.3	0.1	34	20	23	AS7-5715a
M-07-58	X10535	166	168	0.17	0.01	52	0.5	0.1	12	0.1	8	AS7-5715a
M-07-58	X10536	168	170	0.15	0.02	73	0.4	0.1	10	10	8	AS7-5715a
M-07-58	X10537	170	172	0.82	0.03	44	1.3	0.1	12	0.1	11	AS7-5715a
M-07-58	X10538	172	174	0.27	0.02	103	0.6	0.1	18	15	17	AS7-5715a
M-07-58	X10539	174	176	0.24	0.06	64	2.1	50	14	60	38	AS7-5715a
M-07-58	X10540	176	178	0.35	0.14	28	2.6	0.1	26	15	15	AS7-5715a
M-07-58	X10541	178	180	0.81	0.04	198	1.5	0.1	24	0.1	10	AS7-5715a
M-07-58	X10542	180	182	1.11	0.04	82	2.3	0.1	20	0.1	8	AS7-5715a
M-07-58	X10543	182	184	0.76	0.05	83	1.3	0.1	20	40	7	AS7-5715a
M-07-58	X10544	184	186	0.94	0.14	281	2.4	0.1	22	5	12	AS7-5715a
M-07-58	X10545	186	188	1.37	0.14	124	2	0.1	26	35	14	AS7-5715a
M-07-58	X10546	188	190	1.81	0.49	145	7	0.1	48	70	33	AS7-5715a
M-07-58	X10547	190	192	0.94	0.78	143	10.3	30	50	65	37	AS7-5715a
M-07-58	X10548	192	194	1.27	0.91	161	22.5	80	74	225	90	AS7-5715a
M-07-58	X10549	194	196	1.02	0.78	103	14.8	30	62	125	46	AS7-5715a
M-07-58	X10550	196	198	1.19	0.55	235	10.2	0.1	58	90	25	AS7-5715a
M-07-58	X10551	198	200	0.54	0.42	240	11.7	0.1	38	105	44	AS7-5715a
M-07-58	X10552	200	202	0.87	0.36	115	10	0.1	36	95	40	AS7-5715a
M-07-58	X10553	202	204	0.35	0.28	168	12.4	85	4	260	55	AS7-5715a
M-07-58	X10554	204	206	0.36	0.27	275	6.4	10	28	75	24	AS7-5715a
M-07-58	X10555	206	208	0.19	0.20	42	3.4	0.1	16	10	16	AS7-5715a
M-07-58	X10556	208	210	0.56	0.06	102	1.7	0.1	20	15	13	AS7-5715a
M-07-58	X10558	210	212	0.21	0.30	17	3.6	0.1	26	0.1	13	AS7-5715a
M-07-58	X10559	212	214	0.31	0.37	12	3.5	0.1	28	50	18	AS7-5715a
M-07-58	X10560	214	215	0.23	0.33	15	1.8	0.1	14	0.1	547	AS7-5715a
M-07-58	X10562	215	217	0.64	0.44	15	2.2	0.1	14	10	263	AS7-5715a
M-07-58	X10563	217	219	0.35	0.33	19	1.7	0.1	22	30	137	AS7-5715a
M-07-58	X10565	219	221	0.32	0.30	13	4.8	0.1	20	30	104	AS7-5715a
M-07-58	X10566	221	223	0.48	0.31	4	2.1	0.1	32	0.1	93	AS7-5715a
M-07-58	X10567	223	225	2.19	0.31	10	2.6	0.1	22	0.1	23	AS7-5737a
M-07-58	X10568	225	227	0.76	0.38	11	2.7	0.1	30	10	53	AS7-5737a
M-07-58	X10569	227	229	0.33	0.47	12	5.1	20	36	50	34	AS7-5737a
M-07-58	X10570	229	231	0.40	0.63	13	4.9	0.1	36	30	18	AS7-5737a
M-07-58	X10572	231	233	0.71	0.24	14	3.3	0.1	58	0.1	102	AS7-5737a
M-07-58	X10573	233	234.3	0.50	0.27	11	2.2	0.1	38	0.1	37	AS7-5737a
M-07-58	X10574	234.3	235.6	1.28	0.36	10	2.7	0.1	18	0.1	11	AS7-5737a
M-07-58	X10575	235.6	237	1.25	0.28	14	2.4	0.1	18	10	36	AS7-5737a
M-07-58	X10576	237	239	0.67	0.40	13	2.6	0.1	34	0.1	184	AS7-5737a
M-07-58	X10578	239	241	0.92	0.25	17	1.8	0.1	24	0.1	44	AS7-5737a
M-07-58	X10579	241	243	1.04	0.25	9	1.6	0.1	32	0.1	31	AS7-5737a
M-07-58	X10580	243	245	0.81	0.17	14	1.2	0.1	24	0.1	25	AS7-5737a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-58	X10581	245	247	1.54	0.27	14	1.8	0.1	34	0.1	285	AS7-5737a
M-07-58	X10582	247	249	1.16	0.25	12	1.8	0.1	26	0.1	38	AS7-5737a
M-07-58	X10583	249	251	0.68	0.32	13	2.7	0.1	60	0.1	75	AS7-5737a
M-07-58	X10584	251	253	0.74	0.28	15	2.8	0.1	54	0.1	42	AS7-5737a
M-07-58	X10585	253	255	0.68	0.32	11	8.8	100	64	30	136	AS7-5737a
M-07-58	X10586	255	257	0.39	0.23	11	2.1	0.1	38	0.1	70	AS7-5737a
M-07-58	X10587	257	259	0.54	0.20	11	1.6	0.1	34	0.1	39	AS7-5737a
M-07-58	X10588	259	261	0.55	0.24	12	2.6	0.1	32	5	42	AS7-5737a
M-07-58	X10589	261	263	0.85	0.24	11	1.8	0.1	28	0.1	45	AS7-5737a
M-07-58	X10590	263	265	1.07	0.26	13	2.3	0.1	24	10	75	AS7-5737a
M-07-58	X10591	265	267	0.96	0.24	12	1.8	0.1	32	0.1	39	AS7-5737a
M-07-58	X10592	267	269	1.04	0.35	14	2.9	0.1	104	0.1	306	AS7-5737a
M-07-58	X10593	269	271	0.29	0.28	15	2.6	0.1	74	0.1	55	AS7-5737a
M-07-58	X10594	271	273	1.06	0.29	16	2.3	0.1	34	0.1	51	AS7-5737a
M-07-58	X10595	273	275	0.67	0.28	10	2.7	0.1	50	0.1	42	AS7-5737a
M-07-58	X10596	275	277	1.06	0.29	12	2.6	0.1	42	5	53	AS7-5737a
M-07-58	X10597	277	279	0.78	0.20	12	1.7	0.1	24	0.1	43	AS7-5737a
M-07-58	X10598	279	281	1.13	0.30	12	2.5	0.1	28	0.1	45	AS7-5737a
M-07-58	X10599	281	283	1.23	0.40	12	2.6	0.1	30	0.1	24	AS7-5737a
M-07-58	X10600	283	285	0.71	0.53	8	4	0.1	44	0.1	35	AS7-5737a
M-07-58	X10601	285	286	1.32	0.63	10	4.2	0.1	20	0.1	14	AS7-5737a
M-07-58	X10602	286	288	0.39	0.32	9	3.2	25	42	20	35	AS7-5739a
M-07-58	X10603	288	290	0.10	0.10	122	2.4	65	30	30	43	AS7-5739a
M-07-58	X10604	290	292	0.98	0.41	8	7.2	20	72	5	100	AS7-5739a
M-07-58	X10605	292	294	0.84	0.36	12	5.8	25	48	10	48	AS7-5739a
M-07-58	X10606	294	296	0.53	0.31	8	10.1	25	48	10	19	AS7-5739a
M-07-58	X10607	296	297	1.26	0.14	7	13.3	55	22	10	53	AS7-5739a
M-07-58	X10608	297	297.65	0.00	0.03	0.1	1	65	0.1	0.1	385	AS7-5739a
M-07-58	X10609	297.65	299	0.71	0.44	13	60	90	116	165	179	AS7-5739a
M-07-58	X10610	299	301	0.41	0.30	7	64.1	65	296	70	152	AS7-5739a
M-07-58	X10611	301	303	0.37	0.13	12	28.3	55	76	35	135	AS7-5739a
M-07-58	X10612	303	305	0.44	0.21	9	58.3	160	328	165	414	AS7-5739a
M-07-58	X10613	305	307	0.45	0.24	8	23.2	140	46	80	150	AS7-5739a
M-07-58	X10614	307	308.25	0.50	0.49	10	19.4	30	70	30	183	AS7-5739a
M-07-58	X10615	308.25	309.5	0.59	0.49	10	8.9	5	78	0.1	60	AS7-5739a
M-07-58	X10616	309.5	311	0.70	0.24	12	2.6	10	12	0.1	56	AS7-5739a
M-07-58	X10617	311	313	0.81	0.31	11	2.3	15	26	0.1	63	AS7-5739a
M-07-58	X10618	313	315	0.80	0.39	11	2.7	10	32	0.1	58	AS7-5739a
M-07-58	X10619	315	317	0.76	0.35	10	3.5	10	26	0.1	38	AS7-5739a
M-07-58	X10620	317	319	0.72	0.19	10	3.4	15	44	0.1	44	AS7-5739a
M-07-58	X10621	319	321	1.01	0.21	9	2.4	10	18	0.1	45	AS7-5739a
M-07-58	X10622	321	323	1.07	0.31	10	3.4	10	32	0.1	72	AS7-5739a
M-07-58	X10623	323	325	0.37	0.31	10	3	0.1	76	0.1	255	AS7-5739a
M-07-58	X10624	325	327	0.53	0.31	8	3	5	262	5	782	AS7-5739a
M-07-58	X10626	327	329	1.02	0.25	8	2.7	10	50	0.1	54	AS7-5739a
M-07-58	X10627	329	331	1.38	0.27	10	2.6	15	35	0.1	77	AS7-5739a
M-07-58	X10628	331	332.3	1.13	0.31	8	2.5	15	28	0.1	115	AS7-5739a
M-07-58	X10629	332.3	334	1.40	0.49	30	4.2	5	48	0.1	46	AS7-5739a
M-07-58	X10630	334	336	0.36	0.52	6	5.7	20	96	15	114	AS7-5739a
M-07-58	X10631	336	338	0.24	0.31	22	4.1	25	110	20	142	AS7-5739a
M-07-58	X10633	338	340	0.47	0.28	9	2.8	5	46	0.1	99	AS7-5739a
M-07-58	X10634	340	342	0.88	0.25	8	2.3	10	86	0.1	143	AS7-5739a
M-07-58	X10635	342	344	0.93	0.35	9	2.7	5	58	0.1	34	AS7-5739a
M-07-58	X10636	344	346	1.83	0.37	8	3	10	44	0.1	72	AS7-5739a
M-07-58	X10637	346	348	1.13	0.30	8	2.4	10	84	0.1	131	AS7-5718a
M-07-58	X10638	348	350	1.09	0.37	11	3.2	5	68	0.1	66	AS7-5718a
M-07-58	X10639	350	352	1.25	0.28	11	2.3	5	26	0.1	38	AS7-5718a
M-07-58	X10640	352	354	1.74	0.46	10	3.3	5	58	0.1	52	AS7-5718a
M-07-58	X10641	354	356	2.53	0.62	10	4.5	10	80	0.1	81	AS7-5718a
M-07-58	X10642	356	358	1.42	0.29	11	2.1	15	46	0.1	73	AS7-5718a
M-07-58	X10643	358	360	1.58	0.29	10	2.4	10	46	0.1	76	AS7-5718a
M-07-58	X10644	360	362	0.91	0.42	8	3.5	10	114	0.1	34	AS7-5718a
M-07-58	X10645	362	364	1.62	0.49	16	4.1	10	162	0.1	130	AS7-5718a
M-07-58	X10646	364	366	1.92	0.40	12	4.2	15	110	0.1	98	AS7-5718a
M-07-58	X10647	366	368	1.96	0.59	19	8.5	20	80	0.1	115	AS7-5718a
M-07-58	X10648	368	370	0.51	0.33	40	4.8	20	106	10	1125	AS7-5718a
M-07-58	X10649	370	372	1.47	0.49	6	4.4	15	130	0.1	296	AS7-5718a
M-07-58	X10650	372	374	1.04	0.27	8	3.8	25	52	0.1	40	AS7-5718a
M-07-58	X10651	374	376	1.08	0.24	9	2.8	40	36	0.1	86	AS7-5718a
M-07-58	X10652	376	378	1.12	0.24	16	3	20	40	0.1	65	AS7-5718a
M-07-58	X10653	378	380	1.69	0.45	23	6.1	65	28	0.1	52	AS7-5718a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-58	X10654	380	382	2.19	0.36	18	4.3	40	70	0.1	44	AS7-5718a
M-07-58	X10655	382	384	3.60	0.27	17	3.4	45	34	0.1	51	AS7-5718a
M-07-58	X10656	384	386	1.37	0.30	24	3	15	30	0.1	71	AS7-5718a
M-07-58	X10657	386	388	1.42	0.26	13	3.3	5	62	0.1	105	AS7-5718a
M-07-58	X10658	388	390	1.04	0.26	19	5	15	58	0.1	61	AS7-5718a
M-07-58	X10659	390	392	1.31	0.37	21	4.7	25	52	0.1	60	AS7-5718a
M-07-58	X10660	392	394	0.94	0.49	38	5.5	5	240	5	518	AS7-5718a
M-07-58	X10661	394	396	1.16	0.69	32	6.3	15	104	0.1	176	AS7-5718a
M-07-58	X10662	396	398	1.30	0.63	37	5.7	10	52	0.1	41	AS7-5718a
M-07-58	X10663	398	400	1.12	0.86	26	8.4	10	228	0.1	198	AS7-5718a
M-07-58	X10664	400	402	0.87	0.46	21	5.1	5	58	0.1	26	AS7-5718a
M-07-58	X10666	402	404	0.80	0.24	12	2.5	25	48	0.1	79	AS7-5718a
M-07-58	X10667	404	406	1.13	0.25	10	2.9	15	18	0.1	77	AS7-5718a
M-07-58	X10668	406	407.3	0.89	0.45	43	11.4	35	74	15	84	AS7-5718a
M-07-58	X10670	407.3	409	0.34	0.50	16	7.7	10	60	0.1	29	AS7-5718a
M-07-58	X10672	409	411	0.30	0.27	22	3.4	0.1	60	0.1	21	AS7-5723a
M-07-58	X10673	411	413	0.33	0.45	57	4.8	5	76	0.1	78	AS7-5723a
M-07-58	X10674	413	415	0.48	0.23	28	3	10	82	0.1	117	AS7-5723a
M-07-58	X10675	415	417	0.39	0.26	15	3.8	30	46	0.1	35	AS7-5723a
M-07-58	X10676	417	419	0.29	0.26	14	4.6	85	28	5	18	AS7-5723a
M-07-58	X10677	419	421	0.20	0.28	55	4.5	110	30	15	18	AS7-5723a
M-07-58	X10678	421	422.5	0.56	0.68	45	5.2	10	78	0.1	94	AS7-5723a
M-07-58	X10679	422.5	424	1.12	0.17	20	1.7	25	36	15	63	AS7-5723a
M-07-58	X10680	424	426	1.18	0.20	23	2.3	20	34	0.1	45	AS7-5723a
M-07-58	X10681	426	428	0.26	0.31	14	3.2	10	26	0.1	6	AS7-5723a
M-07-58	X10682	428	430	0.21	0.37	19	5.3	50	28	5	16	AS7-5723a
M-07-58	X10683	430	432	0.19	0.19	19	3.5	25	26	0.1	8	AS7-5723a
M-07-58	X10684	432	434	0.16	0.02	18	2.6	60	32	15	12	AS7-5723a
M-07-58	X10685	434	436	0.75	0.03	20	3.3	100	42	0.1	16	AS7-5723a
M-07-58	X10686	436	438	1.31	0.05	39	5.8	175	122	25	39	AS7-5723a
M-07-58	X10687	438	440	0.22	0.03	19	3.2	55	36	0.1	12	AS7-5723a
M-07-58	X10688	440	442	0.15	0.10	41	4.6	95	52	10	15	AS7-5723a
M-07-58	X10689	442	444	0.12	0.04	35	4.9	115	38	20	13	AS7-5723a
M-07-58	X10690	444	446	0.15	0.03	41	3.8	45	62	0.1	15	AS7-5723a
M-07-58	X10691	446	448	0.28	0.03	38	5.3	60	160	20	42	AS7-5723a
M-07-58	X10692	448	450	0.31	0.18	33	5	25	34	0.1	8	AS7-5723a
M-07-58	X10693	450	452	0.39	0.28	22	4.5	20	30	0.1	12	AS7-5723a
M-07-58	X10694	452	454	0.66	0.45	52	5.3	5	62	0.1	50	AS7-5723a
M-07-58	X10695	454	456	1.28	0.68	35	7.7	20	78	0.1	57	AS7-5723a
M-07-58	X10696	456	458	1.54	0.32	27	4.7	20	40	0.1	53	AS7-5723a
M-07-58	X10697	458	460	1.31	0.48	15	6.2	0.1	52	0.1	41	AS7-5723a
M-07-58	X10698	460	462	0.35	0.30	14	5	15	46	0.1	38	AS7-5723a
M-07-58	X10699	462	464	0.34	0.36	22	4.8	10	60	0.1	37	AS7-5723a
M-07-58	X10700	464	466	0.91	0.38	62	5.5	10	114	15	171	AS7-5723a
M-07-58	X10702	466	468	0.69	0.46	22	5.6	10	40	0.1	38	AS7-5723a
M-07-58	X10703	468	470	1.25	0.23	32	3.2	10	28	5	52	AS7-5723a
M-07-58	X10704	470	472	0.77	0.22	33	3.2	5	24	30	39	AS7-5723a
M-07-58	X10706	472	474	0.57	0.38	13	4.2	15	22	0.1	30	AS7-5723a
M-07-58	X10707	474	476	0.74	0.25	27	4.4	0.1	28	15	64	AS7-5733a
M-07-58	X10708	476	478	0.85	0.20	43	4.2	0.1	56	0.1	53	AS7-5733a
M-07-58	X10709	478	480	0.75	0.20	18	3.7	20	30	15	52	AS7-5733a
M-07-58	X10710	480	482	0.90	0.30	20	3.6	0.1	30	0.1	36	AS7-5733a
M-07-58	X10711	482	484	0.75	0.15	26	3.2	30	40	10	65	AS7-5733a
M-07-58	X10712	484	486	0.81	0.38	21	4.1	0.1	38	10	125	AS7-5733a
M-07-58	X10714	486	488	0.71	0.32	61	2.9	0.1	26	30	37	AS7-5733a
M-07-58	X10716	488	490	0.82	0.29	54	3.7	10	32	5	29	AS7-5733a
M-07-58	X10717	490	492	1.00	0.30	25	3.1	45	32	15	40	AS7-5733a
M-07-58	X10718	492	494	0.69	0.27	14	3.1	0.1	26	5	23	AS7-5733a
M-07-58	X10719	494	496	0.59	0.16	12	1.8	10	34	10	60	AS7-5733a
M-07-58	X10720	496	498	0.65	0.13	14	1.5	10	48	20	90	AS7-5733a
M-07-58	X10721	498	500	0.74	0.17	13	2.6	5	30	10	31	AS7-5733a
M-07-58	X10722	500	502	0.85	0.29	11	5.6	5	20	5	39	AS7-5733a
M-07-58	X10723	502	504	0.49	0.23	12	8.9	0.1	38	15	83	AS7-5733a
M-07-58	X10724	504	506	0.50	0.18	10	24.4	75	132	45	224	AS7-5733a
M-07-58	X10725	506	508	0.43	0.20	9	32.3	160	352	105	244	AS7-5733a
M-07-58	X10726	508	509.4	0.42	0.17	17	12.6	15	1036	0.1	625	AS7-5733a
M-07-58	X10727	509.4	511	0.71	0.20	15	6.5	10	56	15	132	AS7-5733a
M-07-58	X10728	511	513	0.48	0.12	18	4.8	5	46	35	119	AS7-5733a
M-07-58	X10729	513	515	0.49	0.20	17	15.7	10	208	15	317	AS7-5733a
M-07-58	X10730	515	517	0.41	0.13	16	6.8	30	40	15	65	AS7-5733a
M-07-58	X10731	517	519	0.60	0.18	17	6.1	30	32	15	33	AS7-5733a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-58	X10732	519	521	0.58	0.16	16	5.2	20	30	5	45	AS7-5733a
M-07-58	X10733	521	523	0.49	0.09	15	3.3	20	64	10	65	AS7-5733a
M-07-58	X10734	523	525	0.73	0.27	12	6.5	15	34	15	40	AS7-5733a
M-07-58	X10735	525	527	0.53	0.23	15	4.8	15	54	20	123	AS7-5733a
M-07-58	X10736	527	529	0.35	0.12	18	2.2	0.1	36	15	81	AS7-5733a
M-07-58	X10737	529	531	0.36	0.15	16	2.1	5	38	15	75	AS7-5733a
M-07-58	X10738	531	533	0.54	0.21	11	3	20	34	0.1	80	AS7-5733a
M-07-58	X10739	533	535	0.55	0.20	19	2.8	0.1	36	30	68	AS7-5733a
M-07-58	X10740	535	537	0.62	0.23	17	4.4	15	30	10	50	AS7-5733a
M-07-58	X10741	537	539	0.43	0.10	14	2.8	20	28	10	70	AS7-5733a
M-07-58	X10742	539	541	0.30	0.10	17	4.1	0.1	28	15	89	AS7-5721a
M-07-58	X10743	541	543	0.40	0.15	14	3.7	0.1	30	15	86	AS7-5721a
M-07-58	X10744	543	545	0.94	0.49	21	11.4	10	36	20	52	AS7-5721a
M-07-58	X10745	545	547	0.35	0.21	12	6.2	20	32	5	41	AS7-5721a
M-07-58	X10746	547	549	0.62	0.22	12	3.3	0.1	28	20	84	AS7-5721a
M-07-58	X10747	549	551	0.41	0.19	22	3.5	10	28	20	66	AS7-5721a
M-07-58	X10748	551	553	0.42	0.22	24	4.1	15	32	15	73	AS7-5721a
M-07-58	X10749	553	555	0.32	0.21	15	4.6	25	28	20	61	AS7-5721a
M-07-58	X10750	555	557	0.61	0.24	14	5.3	15	24	15	54	AS7-5721a
M-07-58	X10751	557	559	0.30	0.09	14	3.4	0.1	22	10	55	AS7-5721a
M-07-58	X10752	559	561	0.36	0.18	13	6.8	15	28	15	56	AS7-5721a
M-07-58	X10753	561	563	0.58	0.23	12	6.1	15	22	15	52	AS7-5721a
M-07-58	X10754	563	565	0.49	0.18	24	4.8	15	26	20	43	AS7-5721a
M-07-58	X10755	565	567	0.21	0.09	21	2.6	5	22	10	57	AS7-5721a
M-07-58	X10756	567	569	0.27	0.18	16	4.8	35	18	15	24	AS7-5721a
M-07-58	X10757	569	571	0.27	0.12	25	3.7	15	20	10	47	AS7-5721a
M-07-58	X10758	571	573	0.30	0.18	16	5.6	30	30	15	25	AS7-5721a
M-07-58	X10759	573	575	0.17	0.15	15	3.9	55	26	15	15	AS7-5721a
M-07-58	X10760	575	577	0.23	0.23	21	9.9	150	32	80	48	AS7-5721a
M-07-58	X10761	577	579	0.33	0.28	13	7.9	30	30	20	15	AS7-5721a
M-07-58	X10762	579	581	0.24	0.19	10	7.5	40	26	20	15	AS7-5721a
M-07-58	X10763	581	583	0.42	0.15	13	4.1	25	20	20	32	AS7-5721a
M-07-58	X10764	583	584.7	0.33	0.23	25	4.6	0.1	18	15	32	AS7-5721a
M-07-58	X10765	584.7	586	0.51	0.25	13	3.9	0.1	28	25	71	AS7-5721a
M-07-58	X10766	586	588	0.86	0.36	12	6.1	10	28	10	42	AS7-5721a
M-07-58	X10767	588	590	0.40	0.20	17	4.2	10	24	10	32	AS7-5721a
M-07-58	X10768	590	592	0.54	0.21	14	4.2	10	26	15	42	AS7-5721a
M-07-58	X10770	592	594	0.54	0.25	37	4.6	10	24	35	45	AS7-5721a
M-07-58	X10772	594	596	0.59	0.21	20	4.8	10	30	15	84	AS7-5721a
M-07-58	X10773	596	598	0.27	0.15	15	2.9	20	26	10	56	AS7-5721a
M-07-58	X10775	598	600	0.25	0.14	21	2.5	20	26	35	66	AS7-5721a
M-07-58	X10776	600	602	0.36	0.20	15	3.4	5	24	0.1	56	AS7-5721a
M-07-58	X10777	602	604	0.29	0.09	14	1.7	15	24	10	43	AS7-5736a
M-07-58	X10778	604	606	0.45	0.11	22	2	25	22	5	46	AS7-5736a
M-07-58	X10779	606	608	0.44	0.19	24	3.4	25	20	0.1	18	AS7-5736a
M-07-58	X10780	608	610	0.41	0.12	21	2.5	45	20	0.1	37	AS7-5736a
M-07-58	X10781	610	612	0.35	0.16	19	3	25	18	5	47	AS7-5736a
M-07-58	X10782	612	614	0.22	0.12	21	4.1	50	20	10	64	AS7-5736a
M-07-58	X10783	614	616	0.23	0.18	19	5.5	25	22	15	100	AS7-5736a
M-07-58	X10784	616	618	0.53	0.20	13	7	20	30	15	110	AS7-5736a
M-07-58	X10785	618	620	0.19	0.16	22	3.1	10	28	5	98	AS7-5736a
M-07-58	X10786	620	622	0.29	0.21	19	4.1	30	28	10	74	AS7-5736a
M-07-58	X10787	622	624	0.39	0.35	17	7.4	10	32	25	95	AS7-5736a
M-07-58	X10788	624	626	0.51	0.20	16	4.9	15	26	10	67	AS7-5736a
M-07-58	X10789	626	628	0.73	0.41	15	10.1	55	22	30	58	AS7-5736a
M-07-58	X10790	628	630	0.42	0.21	16	5.5	35	40	20	91	AS7-5736a
M-07-58	X10791	630	632	0.41	0.27	12	6.9	20	24	0.1	58	AS7-5736a
M-07-58	X10792	632	634	0.80	0.19	13	9.6	30	32	10	92	AS7-5736a
M-07-58	X10793	634	636	0.40	0.16	13	7.3	20	42	5	74	AS7-5736a
M-07-58	X10794	636	638	0.44	0.12	12	3.3	0.1	30	20	74	AS7-5736a
M-07-58	X10795	638	640	0.48	0.14	13	3	0.1	34	15	77	AS7-5736a
M-07-58	X10796	640	642	0.29	0.26	13	4.3	5	32	10	49	AS7-5736a
M-07-58	X10797	642	644	0.60	0.18	25	2.6	0.1	34	15	83	AS7-5736a
M-07-58	X10798	644	646	0.51	0.14	18	1.8	0.1	38	15	94	AS7-5736a
M-07-58	X10799	646	648	0.78	0.24	22	2.9	0.1	46	15	97	AS7-5736a
M-07-58	X10800	648	650	0.68	0.20	15	2.7	0.1	42	20	87	AS7-5736a
M-07-58	X10801	650	652	0.89	0.23	26	2.8	0.1	48	10	101	AS7-5736a
M-07-58	X10802	652	654	0.57	0.34	19	4.1	0.1	46	10	86	AS7-5736a
M-07-58	X10804	654	656	0.53	0.14	21	1.7	0.1	38	15	99	AS7-5736a
M-07-58	X10805	656	658	0.39	0.13	23	1.4	0.1	40	25	109	AS7-5736a
M-07-58	X10807	658	660	0.48	0.19	18	2.5	0.1	44	10	87	AS7-5736a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-58	X10808	660	662	1.34	0.43	17	4.4	0.1	38	15	89	AS7-5736a
M-07-58	X10809	662	664	0.59	0.19	24	2.6	0.1	40	20	82	AS7-5736a
M-07-58	X10810	664	666	0.52	0.16	26	2.3	0.1	40	15	81	AS7-5736a
M-07-58	X10811	666	668	0.57	0.22	36	3.1	0.1	38	15	81	AS7-5736a
M-07-58	X10812	668	670	0.47	0.17	27	3	0.1	32	20	82	AS7-5724a
M-07-58	X10813	670	671.65	0.50	0.16	30	4.5	0.1	36	20	94	AS7-5724a
M-07-58	X10814	671.65	673	0.73	0.46	13	29.7	35	72	20	30	AS7-5724a
M-07-58	X10815	673	675	0.32	0.60	9	25.6	45	38	35	28	AS7-5724a
M-07-58	X10816	675	677	0.39	0.25	9	13.6	20	40	10	16	AS7-5724a
M-07-58	X10817	677	678.6	0.41	0.30	11	11	25	32	10	11	AS7-5724a
M-07-58	X10818	678.6	680	0.25	0.14	13	2.9	10	30	20	74	AS7-5724a
M-07-58	X10819	680	682	0.49	0.23	13	2	0.1	28	30	70	AS7-5724a
M-07-58	X10820	682	684	1.27	0.51	10	4.1	0.1	26	10	71	AS7-5724a
M-07-58	X10821	684	686	0.32	0.20	10	2	0.1	30	5	74	AS7-5724a
M-07-58	X10822	686	688	0.48	0.18	25	2.3	15	44	10	90	AS7-5726aR
M-07-58	X10823	688	690	1.16	0.40	12	3.7	15	32	0.1	80	AS7-5726aR
M-07-58	X10824	690	692	0.46	0.13	15	1.8	20	38	0.1	99	AS7-5726aR
M-07-58	X10825	692	694	0.82	0.12	15	1.7	20	38	20	103	AS7-5726aR
M-07-58	X10826	694	696	0.47	0.18	10	3	20	36	5	51	AS7-5726aR
M-07-58	X10827	696	698	0.58	0.14	13	3	20	32	0.1	55	AS7-5726aR
M-07-58	X10828	698	700	0.65	0.29	13	6.7	10	54	5	15	AS7-5726aR
M-07-58	X10829	700	702	0.27	0.17	25	4.3	20	50	35	39	AS7-5726aR
M-07-58	X10831	702	704	0.41	0.12	15	5.9	0.1	106	10	39	AS7-5726aR
M-07-58	X10832	704	706	0.34	0.36	18	8.9	50	106	20	33	AS7-5726aR
M-07-58	X10833	706	708	0.48	0.65	10	7.5	60	50	30	71	AS7-5726aR
M-07-58	X10834	708	710	0.61	0.31	11	4.9	30	42	10	105	AS7-5726aR
M-07-58	X10835	710	712	0.58	0.26	10	3.3	25	26	5	57	AS7-5726aR
M-07-58	X10837	712	714	0.61	0.11	15	1.9	30	42	15	80	AS7-5726aR
M-07-58	X10838	714	716	0.59	0.22	12	2.6	25	40	20	71	AS7-5726aR
M-07-58	X10839	716	718	0.41	0.13	18	1.8	35	40	40	79	AS7-5726aR
M-07-58	X10840	718	720	0.43	0.13	14	1.7	0.1	30	15	49	AS7-5726aR
M-07-59	X12362	2.5	4.57	1.45	0.32	12	2	0.1	42	10	112	AS7-5729a
M-07-59	X12363	4.57	6	0.74	0.18	17	1.6	0.1	32	20	108	AS7-5729a
M-07-59	X12364	6	8	1.57	0.30	15	2	10	30	10	65	AS7-5729a
M-07-59	X12365	8	10	1.74	0.48	16	2.9	0.1	30	5	48	AS7-5729a
M-07-59	X12366	10	12	1.48	0.27	15	2.1	5	38	20	86	AS7-5729a
M-07-59	X12367	12	14	0.79	0.17	13	1.4	0.1	34	10	79	AS7-5729a
M-07-59	X12368	14	16	0.74	0.23	15	1.9	10	22	15	44	AS7-5729a
M-07-59	X12369	16	18	0.96	0.16	18	19.7	170	42	40	74	AS7-5729a
M-07-59	X12370	18	20	0.93	0.31	15	2.2	40	34	30	65	AS7-5729a
M-07-59	X12371	20	22	1.23	0.29	14	1.8	0.1	116	0.1	148	AS7-5729a
M-07-59	X12372	22	24	1.23	0.28	20	1.9	10	48	30	73	AS7-5729a
M-07-59	X12373	24	26	1.52	0.22	16	1.6	0.1	30	15	42	AS7-5729a
M-07-59	X12374	26	28	0.83	0.14	14	1.4	10	28	10	77	AS7-5729a
M-07-59	X12375	28	30	1.42	0.19	15	2.6	120	82	30	164	AS7-5729a
M-07-59	X12376	30	32	0.74	0.21	15	2	10	34	15	90	AS7-5729a
M-07-59	X12377	32	34	0.76	0.22	17	2.4	5	28	10	98	AS7-5729a
M-07-59	X12378	34	36	0.90	0.19	13	2	15	24	15	40	AS7-5729a
M-07-59	X12379	36	38	0.70	0.24	16	2.6	15	48	10	37	AS7-5729a
M-07-59	X12380	38	40	0.67	0.15	30	1.7	45	22	10	62	AS7-5729a
M-07-59	X12382	40	42	0.96	0.22	20	2.3	20	36	35	61	AS7-5729a
M-07-59	X12384	42	44	0.49	0.17	19	1.5	10	24	15	86	AS7-5729a
M-07-59	X12385	44	46	0.34	0.16	12	1.5	5	22	5	64	AS7-5729a
M-07-59	X12386	46	48	0.86	0.27	10	3	20	26	0.1	79	AS7-5742a
M-07-59	X12387	48	50	1.37	0.34	9	4.9	20	102	0.1	222	AS7-5742a
M-07-59	X12388	50	52	0.89	0.22	14	2.8	15	100	0.1	185	AS7-5742a
M-07-59	X12389	52	54	1.38	0.40	12	4.6	25	30	5	37	AS7-5742a
M-07-59	X12390	54	56	1.14	0.28	12	2.7	15	48	0.1	61	AS7-5742a
M-07-59	X12391	56	58	1.25	0.36	11	4.5	20	30	0.1	14	AS7-5742a
M-07-59	X12392	58	60	0.75	0.25	10	2.6	15	16	0.1	73	AS7-5742a
M-07-59	X12393	60	62	0.61	0.24	14	2.4	15	28	0.1	62	AS7-5742a
M-07-59	X12394	62	64	0.73	0.20	11	2.2	10	22	0.1	63	AS7-5742a
M-07-59	X12395	64	66	0.56	0.29	12	3.8	35	70	10	129	AS7-5742a
M-07-59	X12396	66	68	1.28	0.36	12	4.1	10	30	0.1	59	AS7-5742a
M-07-59	X12397	68	69.7	0.73	0.16	10	2.3	35	36	0.1	158	AS7-5742a
M-07-59	X12398	69.7	72	0.59	0.35	10	3.4	20	86	0.1	64	AS7-5742a
M-07-59	X12399	72	74	0.61	0.20	19	2.1	15	24	0.1	53	AS7-5742a
M-07-59	X12401	74	75.5	0.56	0.15	11	2	25	42	0.1	71	AS7-5742a
M-07-59	X12402	75.5	78	1.00	0.31	12	4.2	85	28	20	56	AS7-5742a
M-07-59	X12403	78	80	0.95	0.38	11	4.9	50	38	10	24	AS7-5742a
M-07-59	X12404	80	82	0.72	0.35	13	0.4	20	40	0.1	43	AS7-5742a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-59	X12406	82	84	0.58	0.37	17	3.5	25	20	0.1	55	AS7-5742a
M-07-59	X12407	84	86	0.88	0.38	11	3.4	35	16	0.1	23	AS7-5742a
M-07-59	X12408	86	88	0.75	0.32	12	3.4	30	68	0.1	71	AS7-5742a
M-07-59	X12409	88	90	1.02	0.45	16	4.2	30	40	10	103	AS7-5742a
M-07-59	X12410	90	92	0.78	0.26	15	5.4	25	32	5	102	AS7-5742a
M-07-59	X12412	92	94	1.29	0.30	11	5.1	30	20	5	46	AS7-5742a
M-07-59	X12413	94	96	1.45	0.46	15	3.6	20	30	5	47	AS7-5742a
M-07-59	X12414	96	98	1.03	0.36	14	4.2	20	36	0.1	101	AS7-5742a
M-07-59	X12415	98	100	1.13	0.38	17	3	15	14	0.1	50	AS7-5742a
M-07-59	X12416	100	102	0.84	0.28	16	2.2	10	22	0.1	58	AS7-5742a
M-07-59	X12417	102	104	0.50	0.27	13	2.3	15	28	0.1	103	AS7-5742a
M-07-59	X12418	104	106	0.68	0.28	16	2.2	15	20	0.1	35	AS7-5742a
M-07-59	X12419	106	108	1.48	0.49	15	4	20	26	0.1	67	AS7-5742a
M-07-59	X12420	108	110	1.13	0.35	11	3.8	20	18	0.1	78	AS7-5742a
M-07-59	X12421	110	112	1.58	0.26	14	12.8	15	72	0.1	75	AS7-5722a
M-07-59	X12422	112	114	1.17	0.40	25	3.7	10	38	5	49	AS7-5722a
M-07-59	X12423	114	116	0.57	0.23	26	1.8	25	34	0.1	52	AS7-5722a
M-07-59	X12424	116	118	0.74	0.30	13	2.5	10	38	5	51	AS7-5722a
M-07-59	X12425	118	120	0.96	0.33	22	2.6	15	62	0.1	50	AS7-5722a
M-07-59	X12426	120	122	0.89	0.33	13	3.3	20	40	0.1	36	AS7-5722a
M-07-59	X12427	122	124	0.67	0.26	42	2.2	20	34	0.1	55	AS7-5722a
M-07-59	X12428	124	126	0.84	0.38	48	5.8	45	42	0.1	33	AS7-5722a
M-07-59	X12429	126	128	0.87	0.30	23	3.5	10	64	0.1	72	AS7-5722a
M-07-59	X12430	128	130	0.84	0.25	16	2.9	25	78	10	211	AS7-5722a
M-07-59	X12431	130	132	1.02	0.48	59	4.9	15	38	10	121	AS7-5722a
M-07-59	X12432	132	134	0.93	0.40	20	3.4	10	40	0.1	37	AS7-5722a
M-07-59	X12433	134	136	0.70	0.32	44	2.8	15	40	0.1	22	AS7-5722a
M-07-59	X12434	136	138	0.75	0.22	63	2.2	15	38	10	31	AS7-5722a
M-07-59	X12435	138	140	0.87	0.21	20	1.9	20	40	10	43	AS7-5722a
M-07-59	X12436	140	142.5	0.80	0.25	19	5.8	30	36	0.1	35	AS7-5722a
M-07-59	X12437	142.5	143.7	0.90	0.32	16	3.2	25	34	10	70	AS7-5722a
M-07-59	X12438	143.7	145.3	1.65	0.52	22	5	15	44	0.1	38	AS7-5722a
M-07-59	X12439	145.3	147	0.66	0.15	14	1.8	15	46	5	60	AS7-5722a
M-07-59	X12441	147	149	0.97	0.23	23	2.6	10	56	10	53	AS7-5722a
M-07-59	X12442	149	151	0.71	0.17	20	1.8	20	42	15	51	AS7-5722a
M-07-59	X12443	151	152.25	0.50	0.21	11	2.1	15	50	0.1	53	AS7-5722a
M-07-59	X12444	152.25	153.9	0.00	0.00	6	0.2	20	96	25	97	AS7-5722a
M-07-59	X12445	153.9	155.6	0.07	0.00	7	0.3	25	78	40	109	AS7-5722a
M-07-59	X12446	155.6	158	0.58	0.18	19	1.9	80	50	10	65	AS7-5722a
M-07-59	X12447	158	160	0.60	0.26	16	2.5	15	158	20	60	AS7-5722a
M-07-59	X12448	160	162	0.40	0.22	15	2	10	46	5	49	AS7-5722a
M-07-59	X12449	162	164	0.42	0.17	22	1.5	20	42	35	50	AS7-5722a
M-07-59	X12451	164	166	0.38	0.19	16	1.8	15	48	5	77	AS7-5722a
M-07-59	X12452	166	168	0.39	0.22	16	2.3	20	78	10	69	AS7-5722a
M-07-59	X12453	168	170	0.50	0.24	28	2.2	30	60	15	46	AS7-5722a
M-07-59	X12454	170	172	0.43	0.23	16	2.5	30	50	5	40	AS7-5722a
M-07-59	X12455	172	174	0.32	0.12	14	1.5	10	42	10	65	AS7-5722a
M-07-59	X12456	174	176	0.58	0.22	15	2.3	15	26	0.1	64	AS7-5720a
M-07-59	X12457	176	178	0.57	0.22	12	2.2	10	26	0.1	57	AS7-5720a
M-07-59	X12458	178	180	0.35	0.10	9	1.3	10	26	0.1	73	AS7-5720a
M-07-59	X12459	180	182	0.56	0.20	14	2.2	15	24	0.1	62	AS7-5720a
M-07-59	X12460	182	184	0.52	0.16	12	1.9	15	22	0.1	66	AS7-5720a
M-07-59	X12462	184	186	0.66	0.26	24	2.8	10	20	0.1	52	AS7-5720a
M-07-59	X12463	186	188	0.75	0.25	25	2.3	20	20	0.1	36	AS7-5720a
M-07-59	X12464	188	190	0.76	0.26	34	2.7	20	16	0.1	46	AS7-5720a
M-07-59	X12465	190	191.9	1.17	0.39	38	4.9	20	18	0.1	38	AS7-5720a
M-07-59	X12466	191.9	193.4	0.41	0.28	189	5.3	25	30	10	24	AS7-5720a
M-07-59	X12467	193.4	194.8	0.38	0.45	309	4.8	5	36	0.1	9	AS7-5720a
M-07-59	X12468	194.8	197	0.49	0.18	24	2.2	10	12	0.1	68	AS7-5720a
M-07-59	X12469	197	199	0.50	0.12	15	1.8	10	10	0.1	52	AS7-5720a
M-07-59	X12470	199	201	0.64	0.21	18	2.8	10	14	0.1	57	AS7-5720a
M-07-59	X12471	201	203	0.64	0.19	11	2.9	35	16	0.1	66	AS7-5720a
M-07-59	X12472	203	205	0.89	0.24	12	2.6	15	16	0.1	54	AS7-5720a
M-07-59	X12473	205	207	0.62	0.22	12	2.5	10	12	0.1	50	AS7-5720a
M-07-59	X12474	207	209	0.59	0.17	10	2.1	15	14	0.1	48	AS7-5720a
M-07-59	X12475	209	211	0.53	0.20	11	4.8	40	38	15	78	AS7-5720a
M-07-59	X12476	211	213	0.48	0.14	12	2.7	35	20	0.1	59	AS7-5720a
M-07-59	X12479	213	215	0.39	0.12	9	1.9	15	12	0.1	72	AS7-5720a
M-07-59	X12480	215	217	0.73	0.23	9	9.3	90	68	5	536	AS7-5720a
M-07-59	X12481	217	219	0.53	0.33	8	46.1	275	158	465	1364	AS7-5720a
M-07-59	X12482	219	221	0.33	0.26	15	10.4	80	200	95	888	AS7-5720a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-59	X12483	221	223	0.41	0.19	20	5.6	75	100	80	279	AS7-5720a
M-07-59	X12484	223	225	0.41	0.25	11	12.3	75	306	55	1131	AS7-5720a
M-07-59	X12485	225	227	0.58	0.42	8	76.8	135	330	230	1454	AS7-5720a
M-07-59	X12486	227	229.65	0.51	0.25	12	23.4	70	146	40	436	AS7-5720a
M-07-59	X12487	229.65	232	0.86	0.19	13	94.4	80	806	25	2688	AS7-5720a
M-07-59	X12488	232	234.5	0.84	0.28	13	4.3	35	14	0.1	86	AS7-5720a
M-07-59	X12489	234.5	236.25	0.66	0.55	46	11.8	30	60	10	37	AS7-5720a
M-07-59	X12490	236.25	238.5	0.31	0.14	16	7.7	35	222	10	1378	AS7-5720a
M-07-59	X12491	238.5	240.5	0.57	0.35	23	12	20	118	15	1612	AS7-5730a
M-07-59	X12492	240.5	242.2	0.72	0.27	24	13.1	15	588	20	1917	AS7-5730a
M-07-59	X12493	242.2	244.85	0.34	0.25	22	6.8	10	214	0.1	857	AS7-5730a
M-07-59	X12494	244.85	247	0.56	0.31	25	8.1	15	140	5	248	AS7-5730a
M-07-59	X12495	247	249	0.83	0.28	21	4.6	0.1	46	20	78	AS7-5730a
M-07-59	X12496	249	251	1.34	0.58	15	8.6	0.1	26	5	39	AS7-5730a
M-07-59	X12497	251	253	1.27	0.80	18	12.4	0.1	36	20	45	AS7-5730a
M-07-59	X12498	253	255	1.02	0.81	15	18.7	15	42	15	29	AS7-5730a
M-07-59	X12499	255	257	1.12	0.38	15	5.2	0.1	26	5	52	AS7-5730a
M-07-59	X12500	257	259	0.96	0.35	22	4.9	0.1	28	5	92	AS7-5730a
M-07-59	X12501	259	261	0.82	0.26	17	4.5	0.1	28	15	122	AS7-5730a
M-07-59	X12502	261	263	1.02	0.27	30	5.9	0.1	26	5	75	AS7-5730a
M-07-59	X12503	263	265	0.95	0.27	34	11	35	42	35	119	AS7-5730a
M-07-59	X12504	265	267.01	0.62	0.19	32	24.1	25	266	0.1	296	AS7-5730a
M-07-59	X12505	267.01	269	0.78	0.14	69	8.7	40	36	15	91	AS7-5730a
M-07-59	X12506	269	271	0.53	0.15	29	6.1	15	30	15	87	AS7-5730a
M-07-59	X12507	271	273	0.52	0.18	52	4.8	0.1	34	20	67	AS7-5730a
M-07-59	X12508	273	275	0.66	0.22	18	3.6	10	24	5	43	AS7-5730a
M-07-59	X12509	275	277	0.30	0.12	34	1.6	0.1	26	10	71	AS7-5730a
M-07-59	X12510	277	279	0.54	0.25	176	2.4	5	32	20	47	AS7-5730a
M-07-59	X12511	279	281	0.34	0.14	48	2.5	15	24	25	49	AS7-5730a
M-07-59	X12512	281	283	0.46	0.15	68	1.7	0.1	26	10	45	AS7-5730a
M-07-59	X12513	283	285	0.30	0.10	32	0.9	10	22	15	47	AS7-5730a
M-07-59	X12514	285	287	0.27	0.08	27	0.9	0.1	28	10	50	AS7-5730a
M-07-59	X12515	287	289	0.35	0.11	20	1.1	0.1	26	20	42	AS7-5730a
M-07-59	X12516	289	291	0.52	0.18	30	2	0.1	24	10	36	AS7-5730a
M-07-59	X12517	291	293	0.55	0.21	21	2.2	15	30	10	39	AS7-5730a
M-07-59	X12518	293	295	0.35	0.15	16	1.5	30	38	25	98	AS7-5730a
M-07-59	X12519	295	297	0.38	0.13	12	4	10	24	10	55	AS7-5730a
M-07-59	X12522	297	299	0.28	0.05	20	3.4	5	22	15	63	AS7-5730a
M-07-59	X12523	299	301	0.33	0.13	13	8.5	50	32	0.1	55	AS7-5730a
M-07-59	X12524	301	303	0.32	0.12	11	23.2	45	124	0.1	94	AS7-5730a
M-07-59	X12526	303	305	0.27	0.19	16	10.6	20	84	10	59	AS7-5731a
M-07-59	X12527	305	307	0.21	0.10	31	9.3	35	162	5	449	AS7-5731a
M-07-59	X12528	307	309	0.30	0.15	27	126	190	200	160	609	AS7-5731a
M-07-59	X12529	309	311	0.98	0.17	27	100	160	266	50	630	AS7-5731a
M-07-59	X12530	311	313	0.50	0.34	12	24.4	55	56	0.1	97	AS7-5731a
M-07-59	X12532	313	315	0.31	0.15	22	5.2	35	26	15	53	AS7-5731a
M-07-59	X12533	315	317	0.23	0.06	22	1.2	20	22	0.1	47	AS7-5731a
M-07-59	X12534	317	319	0.74	0.24	20	2.9	45	28	20	58	AS7-5731a
M-07-59	X12535	319	321	0.44	0.18	16	8.5	35	262	15	261	AS7-5731a
M-07-59	X12536	321	323	0.88	0.33	14	33.9	50	42	5	136	AS7-5731a
M-07-59	X12537	323	325	0.47	0.16	14	14.6	55	42	30	113	AS7-5731a
M-07-59	X12538	325	327	0.73	0.38	18	26.7	80	40	25	114	AS7-5731a
M-07-59	X12539	327	329	0.58	0.18	20	12.6	120	38	25	126	AS7-5731a
M-07-59	X12540	329	331	0.61	0.08	31	4.6	100	42	75	173	AS7-5731a
M-07-59	X12541	331	333	0.35	0.18	21	7	65	80	0.1	250	AS7-5731a
M-07-59	X12542	333	335	0.33	0.15	43	5.6	30	38	55	118	AS7-5731a
M-07-59	X12543	335	337	0.22	0.09	12	6.5	50	74	10	124	AS7-5731a
M-07-59	X12544	337	339	0.40	0.13	19	4.8	35	34	25	95	AS7-5731a
M-07-59	X12545	339	341	0.24	0.09	19	2.7	30	26	5	60	AS7-5731a
M-07-59	X12546	341	343	0.34	0.09	20	0.9	30	36	10	66	AS7-5731a
M-07-59	X12547	343	345	0.32	0.37	15	2.6	5	42	10	49	AS7-5731a
M-07-59	X12548	345	347	0.26	0.10	18	0.9	10	28	15	58	AS7-5731a
M-07-59	X12549	347	349	0.47	0.17	10	1.8	10	26	0.1	41	AS7-5731a
M-07-59	X12550	349	351	0.28	0.17	12	2.1	10	32	20	71	AS7-5731a
M-07-59	X12551	351	353	0.39	0.15	17	3.5	20	30	15	84	AS7-5731a
M-07-59	X12552	353	355	0.39	0.22	15	8.4	30	262	15	307	AS7-5731a
M-07-59	X12553	355	357	0.39	0.14	17	5.7	45	104	20	205	AS7-5731a
M-07-59	X12554	357	359	0.29	0.13	21	5.1	25	80	20	91	AS7-5731a
M-07-59	X12555	359	361	0.42	0.19	24	18.2	45	150	10	364	AS7-5731a
M-07-59	X12556	361	363	0.52	0.08	19	2.9	45	38	15	77	AS7-5731a
M-07-59	X12557	363	365	0.55	0.28	14	5.3	40	44	20	48	AS7-5731a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-59	X12558	365	367	0.69	0.23	10	4.3	20	32	20	76	AS7-5731a
M-07-59	X12559	367	369	0.23	0.09	14	1.7	15	36	35	80	AS7-5731a
M-07-59	X12561	369	371	0.24	0.06	18	0.9	5	30	15	71	AS7-5734a
M-07-59	X12562	371	373	0.24	0.10	21	0.8	0.1	32	10	51	AS7-5734a
M-07-59	X12563	373	375	0.14	0.11	19	1	0.1	32	10	58	AS7-5734a
M-07-59	X12564	375	377	0.38	0.11	10	0.8	0.1	28	10	70	AS7-5734a
M-07-59	X12565	377	379	0.50	0.15	53	1.4	10	82	10	85	AS7-5734a
M-07-59	X12566	379	381	0.61	0.23	16	2	0.1	26	15	61	AS7-5734a
M-07-59	X12567	381	383	0.34	0.10	13	0.8	0.1	22	5	51	AS7-5734a
M-07-59	X12568	383	385	0.30	0.10	13	0.8	0.1	26	15	54	AS7-5734a
M-07-59	X12569	385	387	0.42	0.15	10	1	0.1	22	15	55	AS7-5734a
M-07-59	X12570	387	389	0.43	0.16	27	1	0.1	24	10	47	AS7-5734a
M-07-59	X12571	389	391	0.27	0.09	57	0.8	0.1	28	10	52	AS7-5734a
M-07-59	X12572	391	393	0.31	0.13	24	1.3	0.1	28	10	57	AS7-5734a
M-07-59	X12573	393	395	0.52	0.09	29	1.1	0.1	22	15	64	AS7-5734a
M-07-59	X12574	395	397	0.40	0.16	31	1.6	5	36	10	57	AS7-5734a
M-07-59	X12575	397	399	0.33	0.08	39	1.2	10	30	15	56	AS7-5734a
M-07-59	X12576	399	401	0.30	0.10	53	1.6	10	24	10	46	AS7-5734a
M-07-59	X12577	401	403	0.49	0.29	23	6.1	10	70	15	61	AS7-5734a
M-07-59	X12580	403	405	0.51	0.20	158	3.4	5	30	10	52	AS7-5734a
M-07-59	X12581	405	407	0.16	0.06	58	0.8	0.1	32	20	47	AS7-5734a
M-07-59	X12582	407	409	0.34	0.08	143	0.9	10	32	15	47	AS7-5734a
M-07-59	X12583	409	411	0.17	0.07	35	1	10	26	5	39	AS7-5734a
M-07-59	X12584	411	413	0.26	0.07	36	1.2	0.1	48	15	55	AS7-5734a
M-07-59	X12585	413	415	0.17	0.05	55	0.9	0.1	24	10	45	AS7-5734a
M-07-59	X12586	415	417	0.29	0.08	45	1.3	15	28	10	45	AS7-5734a
M-07-59	X12587	417	419	0.28	0.07	51	1.1	10	28	10	48	AS7-5734a
M-07-59	X12588	419	421	0.33	0.05	19	1.3	15	60	15	74	AS7-5734a
M-07-59	X12589	421	423	0.43	0.10	33	2.2	40	36	25	55	AS7-5734a
M-07-59	X12590	423	425	0.46	0.20	95	3.7	10	40	15	57	AS7-5734a
M-07-59	X12591	425	427	0.20	0.08	50	1.1	5	28	10	50	AS7-5734a
M-07-59	X12592	427	429	0.96	0.06	62	1.6	30	36	10	37	AS7-5734a
M-07-59	X12593	429	431	0.30	0.10	194	4.1	15	40	10	75	AS7-5734a
M-07-59	X12594	431	433	0.28	0.10	73	4.5	5	38	5	55	AS7-5734a
M-07-59	X12595	433	435	0.58	0.17	100	1.4	0.1	30	5	56	AS7-5734a
M-07-59	X12596	435	437.39	0.44	0.13	82	1.3	0.1	38	0.1	65	AS7-5726aR
M-07-60	X14228	1.22	4	0.10	0.01	3	0.7	0.1	30	0.1	34	AS7-5735a
M-07-60	X14229	4	6	0.13	0.02	9	0.7	0.1	56	0.1	40	AS7-5735a
M-07-60	X14231	6	8	0.16	0.02	5	0.6	0.1	32	10	42	AS7-5735a
M-07-60	X14232	8	10	0.17	0.02	14	0.5	0.1	26	15	40	AS7-5735a
M-07-60	X14233	10	12	0.09	0.02	7	0.5	0.1	26	0.1	30	AS7-5735a
M-07-60	X14234	12	14	0.09	0.01	7	0.8	0.1	32	0.1	30	AS7-5735a
M-07-60	X14235	14	16	0.15	0.02	8	1.3	0.1	32	10	61	AS7-5735a
M-07-60	X14236	16	18	0.10	0.02	5	4.2	15	224	30	231	AS7-5735a
M-07-60	X14237	18	20	0.24	0.01	7	1	0.1	50	5	84	AS7-5735a
M-07-60	X14238	20	22	0.16	0.01	6	0.7	0.1	32	10	50	AS7-5735a
M-07-60	X14239	22	24	0.07	0.01	17	0.9	0.1	36	10	68	AS7-5735a
M-07-60	X14241	24	26	0.14	0.02	7	0.6	0.1	32	0.1	26	AS7-5735a
M-07-60	X14242	26	28	0.15	0.03	8	0.7	0.1	22	0.1	23	AS7-5735a
M-07-60	X14243	28	30	0.12	0.02	14	0.4	0.1	38	20	51	AS7-5735a
M-07-60	X14244	30	32	0.13	0.02	7	0.4	0.1	46	15	84	AS7-5735a
M-07-60	X14245	32	34	0.16	0.03	10	0.6	0.1	40	15	71	AS7-5735a
M-07-60	X14246	34	36	0.16	0.02	8	0.5	25	60	15	55	AS7-5728a
M-07-60	X14247	36	38	0.22	0.02	9	0.5	10	48	10	42	AS7-5728a
M-07-60	X14248	38	40	0.27	0.05	54	0.6	15	48	35	45	AS7-5728a
M-07-60	X14249	40	42	0.28	0.05	15	0.7	15	58	25	63	AS7-5728a
M-07-60	X14250	42	44	0.21	0.05	38	1.4	0.1	50	10	18	AS7-5728a
M-07-60	X14251	44	46	0.15	0.05	44	1.1	0.1	26	0.1	9	AS7-5728a
M-07-60	X14252	46	48	0.13	0.02	125	0.6	10	38	0.1	3	AS7-5728a
M-07-60	X14253	48	50	0.13	0.04	48	0.8	0.1	42	0.1	11	AS7-5728a
M-07-60	X14254	50	52	0.16	0.04	23	0.7	0.1	34	0.1	25	AS7-5728a
M-07-60	X14255	52	54.2	0.46	0.05	29	2.1	10	50	0.1	37	AS7-5728a
M-07-60	X14256	54.2	56.4	0.30	0.05	55	0.6	20	48	15	57	AS7-5728a
M-07-60	X14257	56.4	58	0.26	0.07	18	0.6	20	46	10	73	AS7-5728a
M-07-60	X14258	58	60	0.28	0.09	471	1.2	15	48	10	44	AS7-5728a
M-07-60	X14259	60	62	0.68	0.17	45	1.9	10	60	25	166	AS7-5728a
M-07-60	X14260	62	64	0.43	0.09	163	1.1	10	50	5	62	AS7-5728a
M-07-60	X14262	64	66	0.42	0.09	113	1.2	25	46	0.1	56	AS7-5728a
M-07-60	X14263	66	68	0.46	0.14	60	1.8	10	36	0.1	43	AS7-5728a
M-07-60	X14264	68	70	0.65	0.20	36	4.5	10	80	10	66	AS7-5728a
M-07-60	X14265	70	72	0.61	0.20	36	3.9	30	54	15	152	AS7-5728a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-60	X14267	72	74.15	0.60	0.22	46	2.2	15	98	15	54	AS7-5728a
M-07-60	X14268	74.15	76	0.28	0.17	105	2	25	150	0.1	259	AS7-5728a
M-07-60	X14269	76	78	0.20	0.10	32	2.4	20	132	0.1	75	AS7-5728a
M-07-60	X14270	78	80	0.26	0.10	31	2.3	15	46	15	50	AS7-5728a
M-07-60	X14271	80	82	0.29	0.20	28	6.2	30	118	25	110	AS7-5728a
M-07-60	X14272	82	84	0.23	0.19	41	4	15	44	15	69	AS7-5728a
M-07-60	X14273	84	86	0.28	0.14	42	6.7	45	108	35	37	AS7-5728a
M-07-60	X14274	86	88	0.52	0.12	204	4	5	536	5	57	AS7-5728a
M-07-60	X14276	88	90	0.31	0.20	59	3.6	0.1	62	0.1	105	AS7-5728a
M-07-60	X14277	90	92	0.15	0.05	68	2	0.1	56	10	40	AS7-5728a
M-07-60	X14278	92	94	0.21	0.11	60	4.6	25	92	25	45	AS7-5728a
M-07-60	X14279	94	96	0.35	0.22	61	5.4	15	80	20	35	AS7-5728a
M-07-60	X14280	96	98	0.78	0.19	82	3.8	25	136	0.1	315	AS7-5728a
M-07-60	X14281	98	100	0.29	0.15	55	3.9	0.1	84	10	218	AS7-5727a
M-07-60	X14282	100	102	0.50	0.21	55	6.3	0.1	144	15	442	AS7-5727a
M-07-60	X14283	102	104	0.11	0.12	120	2	0.1	108	15	58	AS7-5727a
M-07-60	X14284	104	106	0.11	0.11	72	3.6	60	88	85	104	AS7-5727a
M-07-60	X14285	106	108	0.22	0.18	114	7.7	70	198	130	1316	AS7-5727a
M-07-60	X14286	108	110	0.19	0.13	86	3.2	0.1	178	15	493	AS7-5727a
M-07-60	X14287	110	112	0.23	0.11	117	1.9	0.1	78	25	69	AS7-5727a
M-07-60	X14288	112	114	0.18	0.09	205	2.7	0.1	726	5	596	AS7-5727a
M-07-60	X14289	114	116	0.23	0.14	86	4.2	15	280	20	814	AS7-5727a
M-07-60	X14290	116	118	0.16	0.09	86	2.3	10	324	15	314	AS7-5727a
M-07-60	X14291	118	120	0.18	0.10	90	6.6	0.1	2024	10	2541	AS7-5727a
M-07-60	X14293	120	122	0.18	0.09	65	5	15	324	15	116	AS7-5727a
M-07-60	X14294	122	124.1	1.45	0.28	107	4.8	45	108	15	216	AS7-5727a
M-07-60	X14296	124.1	126	1.22	0.12	110	2.4	35	80	15	93	AS7-5727a
M-07-60	X14297	126	128	0.17	0.08	55	1.9	30	270	15	377	AS7-5727a
M-07-60	X14298	128	130	0.22	0.06	63	1.2	30	68	35	58	AS7-5727a
M-07-60	X14299	130	132	0.31	0.07	69	1.1	35	54	15	58	AS7-5727a
M-07-60	X14300	132	134	0.18	0.05	37	1.1	30	50	15	68	AS7-5727a
M-07-60	X14301	134	136	0.14	0.06	46	1.4	25	184	15	313	AS7-5727a
M-07-60	X14303	136	138	0.42	0.12	166	1.6	30	50	10	54	AS7-5727a
M-07-60	X14304	138	140	0.36	0.09	78	2.1	25	270	20	1191	AS7-5727a
M-07-60	X14305	140	140.9	0.20	0.08	261	2.1	30	90	15	1759	AS7-5727a
M-07-60	X14306	140.9	142.9	0.26	0.07	80	6.2	70	114	50	81	AS7-5727a
M-07-60	X14307	142.9	145	0.28	0.11	89	1.8	15	64	10	216	AS7-5727a
M-07-60	X14308	145	147	0.42	0.13	103	2.6	25	66	40	189	AS7-5727a
M-07-60	X14309	147	149	0.27	0.10	199	2.8	30	150	10	447	AS7-5727a
M-07-60	X14310	149	151	0.56	0.13	97	1.4	20	48	10	86	AS7-5727a
M-07-60	X14311	151	153	0.28	0.09	102	1.5	30	76	20	103	AS7-5727a
M-07-60	X14312	153	155	1.04	0.24	89	2.7	5	50	15	68	AS7-5727a
M-07-60	X14313	155	157	0.78	0.18	87	1.8	15	44	15	74	AS7-5727a
M-07-60	X14314	157	159	0.60	0.13	71	1.3	15	52	20	74	AS7-5727a
M-07-60	X14315	159	161	0.48	0.12	110	1.4	15	56	15	73	AS7-5727a
M-07-60	X14316	161	163	0.37	0.10	78	1	0.1	36	15	81	AS7-5716a
M-07-60	X14317	163	165	0.40	0.11	84	1.4	0.1	34	15	69	AS7-5716a
M-07-60	X14318	165	167	0.29	0.08	131	0.9	0.1	74	15	180	AS7-5716a
M-07-60	X14319	167	169	0.66	0.15	76	1.5	0.1	36	30	69	AS7-5716a
M-07-60	X14320	169	171	0.41	0.13	61	1.2	0.1	34	20	85	AS7-5716a
M-07-60	X14321	171	173	0.45	0.12	90	1.9	0.1	52	10	117	AS7-5716a
M-07-60	X14322	173	175	0.25	0.09	51	2.1	5	42	5	230	AS7-5716a
M-07-60	X14323	175	177	0.37	0.11	64	1.5	0.1	36	15	69	AS7-5716a
M-07-60	X14324	177	179	0.48	0.10	64	1.2	0.1	36	10	68	AS7-5716a
M-07-60	X14325	179	181	0.35	0.09	84	1.3	0.1	44	25	98	AS7-5716a
M-07-60	X14327	181	183	0.35	0.09	97	1	0.1	38	15	85	AS7-5716a
M-07-60	X14328	183	185	0.62	0.12	74	1.3	0.1	36	10	83	AS7-5716a
M-07-60	X14329	185	187	0.42	0.12	70	1.4	0.1	48	10	1181	AS7-5716a
M-07-60	X14330	187	189	0.72	0.14	76	1.8	0.1	34	75	83	AS7-5716a
M-07-60	X14331	189	191	0.59	0.16	72	1.9	0.1	36	10	64	AS7-5716a
M-07-60	X14332	191	193	0.48	0.13	99	1.3	0.1	38	10	79	AS7-5716a
M-07-60	X14333	193	195	0.33	0.08	69	1.5	0.1	42	10	333	AS7-5716a
M-07-60	X14334	195	197	0.43	0.12	109	1.6	0.1	44	10	130	AS7-5716a
M-07-60	X14335	197	199	0.51	0.17	142	2	0.1	36	10	55	AS7-5716a
M-07-60	X14336	199	201	0.34	0.11	95	1.4	0.1	38	65	121	AS7-5716a
M-07-60	X14337	201	203	0.57	0.13	62	1.6	0.1	32	10	54	AS7-5716a
M-07-60	X14339	203	205	0.52	0.15	104	2.8	0.1	58	65	167	AS7-5716a
M-07-60	X14340	205	207	0.56	0.29	65	6.4	0.1	146	0.1	321	AS7-5716a
M-07-60	X14341	207	209	0.28	0.10	59	2	0.1	52	10	235	AS7-5716a
M-07-60	X14342	209	211	0.35	0.07	54	1.3	0.1	40	15	116	AS7-5716a
M-07-60	X14343	211	213.65	0.63	0.21	167	2.3	0.1	40	10	58	AS7-5716a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-60	X14344	213.65	216.7	0.43	0.09	52	1.1	0.1	28	5	59	AS7-5716a
M-07-60	X14345	216.7	219.14	0.63	0.13	59	1.4	0.1	38	10	47	AS7-5716a
M-07-60	X14346	219.14	221	0.64	0.17	93	1.6	0.1	28	15	48	AS7-5716a
M-07-60	X14347	221	223	0.34	0.09	66	1.2	0.1	32	10	55	AS7-5716a
M-07-60	X14348	223	225	0.32	0.07	47	1.2	5	54	0.1	90	AS7-5716a
M-07-60	X14350	225	227	0.65	0.16	50	1.7	0.1	36	0.1	45	AS7-5716a
M-07-60	X14351	227	229	0.51	0.14	43	1.4	10	10	0.1	65	AS7-5714a
M-07-60	X14352	229	231	0.31	0.12	51	1.1	10	8	0.1	50	AS7-5714a
M-07-60	X14353	231	233	0.37	0.13	48	1.5	10	8	0.1	43	AS7-5714a
M-07-60	X14354	233	235	0.31	0.10	50	1.4	15	28	0.1	92	AS7-5714a
M-07-60	X14355	235	237	0.81	0.30	105	2.8	10	50	0.1	62	AS7-5714a
M-07-60	X14356	237	239	0.54	0.13	65	1.4	15	10	0.1	68	AS7-5714a
M-07-60	X14357	239	241	0.32	0.13	57	1.4	10	10	0.1	61	AS7-5714a
M-07-60	X14359	241	243	0.40	0.12	90	1.3	10	8	0.1	78	AS7-5714a
M-07-60	X14360	243	245	1.61	0.44	147	4.7	15	34	0.1	89	AS7-5714a
M-07-60	X14361	245	247	0.32	0.08	39	1.2	15	20	0.1	80	AS7-5714a
M-07-60	X14362	247	249	0.34	0.11	87	1.4	15	10	0.1	66	AS7-5714a
M-07-60	X14363	249	251	0.42	0.15	68	1.6	15	28	0.1	84	AS7-5714a
M-07-60	X14364	251	253	0.42	0.10	52	1.6	10	8	0.1	62	AS7-5714a
M-07-60	X14365	253	255	0.46	0.14	83	0.9	15	48	0.1	82	AS7-5714a
M-07-60	X14366	255	257	0.37	0.15	41	1.8	15	58	0.1	103	AS7-5714a
M-07-60	X14367	257	259	0.36	0.10	172	1.2	15	14	0.1	86	AS7-5714a
M-07-60	X14368	259	261	0.32	0.09	56	1.4	20	14	0.1	86	AS7-5714a
M-07-60	X14369	261	263	0.38	0.11	127	1.1	15	26	0.1	77	AS7-5714a
M-07-60	X14370	263	265	0.25	0.08	42	0.7	10	10	0.1	55	AS7-5714a
M-07-60	X14371	265	267	0.34	0.11	37	1.1	15	6	0.1	60	AS7-5714a
M-07-60	X14372	267	269	0.66	0.23	74	2.6	15	16	0.1	55	AS7-5714a
M-07-60	X14373	269	271	0.31	0.10	55	0.8	10	6	0.1	43	AS7-5714a
M-07-60	X14374	271	273	0.80	0.18	83	1.4	15	10	0.1	55	AS7-5714a
M-07-60	X14376	273	275	0.27	0.08	60	0.8	10	8	0.1	47	AS7-5714a
M-07-60	X14377	275	277	0.44	0.18	86	1.6	15	6	0.1	52	AS7-5714a
M-07-60	X14378	277	279	0.28	0.11	67	1.1	15	20	0.1	62	AS7-5714a
M-07-60	X14379	279	281	0.25	0.10	54	0.9	10	8	0.1	53	AS7-5714a
M-07-60	X14380	281	283	0.22	0.07	36	0.7	10	8	0.1	42	AS7-5714a
M-07-60	X14381	283	285	0.16	0.07	40	0.8	10	14	0.1	54	AS7-5714a
M-07-60	X14382	285	287	0.39	0.11	41	1.3	10	16	0.1	110	AS7-5714a
M-07-60	X14383	287	289	0.44	0.17	32	1.6	10	14	0.1	61	AS7-5714a
M-07-60	X14384	289	291	0.32	0.12	32	1.5	15	20	0.1	124	AS7-5714a
M-07-60	X14385	291	293	0.37	0.14	57	2	15	130	0.1	368	AS7-5714a
M-07-60	X14386	293	294	0.53	0.18	92	2.2	20	82	20	107	AS7-5732a
M-07-60	X14387	294	296	0.43	0.17	51	2.1	0.1	48	20	84	AS7-5732a
M-07-60	X14388	296	298	0.44	0.13	172	1.6	15	52	10	91	AS7-5732a
M-07-60	X14389	298	300	0.36	0.11	63	1.5	15	36	30	89	AS7-5732a
M-07-60	X14390	300	302	0.52	0.13	47	2	75	34	20	61	AS7-5732a
M-07-60	X14391	302	303	0.70	0.15	57	2.4	45	52	0.1	89	AS7-5732a
M-07-60	X14392	303	305	0.30	0.11	40	1.1	10	42	20	97	AS7-5732a
M-07-60	X14393	305	307	0.71	0.37	148	2.7	25	56	25	78	AS7-5732a
M-07-60	X14394	307	309	0.36	0.13	74	1.2	25	42	30	85	AS7-5732a
M-07-60	X14396	309	311	0.42	0.23	47	2	15	40	25	78	AS7-5732a
M-07-60	X14397	311	313	0.51	0.22	185	3.3	25	134	20	116	AS7-5732a
M-07-60	X14398	313	315	0.79	0.38	82	4.5	10	50	20	99	AS7-5732a
M-07-60	X14399	315	317	0.46	0.16	54	1.5	10	40	25	89	AS7-5732a
M-07-60	X14400	317	319	0.43	0.15	51	1.6	20	48	20	91	AS7-5732a
M-07-60	X14401	319	321	0.27	0.12	37	1.4	15	44	15	94	AS7-5732a
M-07-60	X14402	321	323	0.35	0.12	43	1.5	15	40	25	102	AS7-5732a
M-07-60	X14403	323	325	0.40	0.13	48	1.3	20	40	15	78	AS7-5732a
M-07-60	X14404	325	327	0.41	0.16	46	1.7	20	50	20	114	AS7-5732a
M-07-60	X14405	327	329	0.87	0.21	55	1.9	25	52	20	92	AS7-5732a
M-07-60	X14406	329	331	0.48	0.18	60	1.7	25	48	20	82	AS7-5732a
M-07-60	X14407	331	333	0.40	0.15	58	1.3	25	46	40	82	AS7-5732a
M-07-60	X14408	333	334	0.40	0.11	73	2.2	90	44	25	80	AS7-5732a
M-07-60	X14409	334	336	0.56	0.15	85	3.1	85	50	15	45	AS7-5732a
M-07-60	X14410	336	338	0.42	0.17	126	2.3	45	52	20	61	AS7-5732a
M-07-60	X14411	338	340	0.22	0.11	74	0.8	30	52	25	82	AS7-5732a
M-07-60	X14413	340	342	0.31	0.14	56	1.2	35	54	20	78	AS7-5732a
M-07-60	X14414	342	344	0.46	0.23	65	2	35	56	25	85	AS7-5732a
M-07-60	X14415	344	346	0.34	0.12	54	1.1	30	46	20	86	AS7-5732a
M-07-60	X14416	346	348	0.25	0.12	77	1	30	154	15	91	AS7-5732a
M-07-60	X14417	348	350	0.24	0.10	44	1.2	45	62	20	114	AS7-5732a
M-07-60	X14418	350	352	0.29	0.09	47	0.9	25	50	40	95	AS7-5732a
M-07-60	X14419	352	354	0.48	0.15	60	2.5	120	76	20	93	AS7-5732a

HOLE ID	SAMPLE NO.	FROM	TO	AU GPT	CU PCT	MO PPM	AG PPM	AS PPM	PB PPM	SB PPM	ZN PPM	LAB FILE#
M-07-60	X14420	354	356	0.32	0.16	54	1.8	35	68	30	102	AS7-5732a
M-07-60	X14421	356	358	0.34	0.11	55	1.4	0.1	38	15	74	AS7-5725a
M-07-60	X14422	358	360	0.28	0.10	45	1.4	0.1	40	15	75	AS7-5725a
M-07-60	X14423	360	362	0.29	0.13	56	1.7	0.1	38	15	67	AS7-5725a
M-07-60	X14424	362	364	0.25	0.11	59	1.2	0.1	36	15	67	AS7-5725a
M-07-60	X14425	364	366	0.24	0.12	61	1.2	0.1	40	25	74	AS7-5725a
M-07-60	X14426	366	368	0.19	0.09	293	1.4	0.1	40	10	81	AS7-5725a
M-07-60	X14427	368	370	0.28	0.10	62	0.9	0.1	36	10	77	AS7-5725a
M-07-60	X14428	370	372	0.16	0.09	93	1.2	0.1	34	45	93	AS7-5725a
M-07-60	X14431	372	374	0.21	0.09	70	1.1	0.1	34	30	99	AS7-5725a
M-07-60	X14432	374	376	0.36	0.13	45	1.7	0.1	62	20	121	AS7-5725a
M-07-60	X14433	376	378	0.38	0.17	87	2.8	0.1	44	15	146	AS7-5725a
M-07-60	X14434	378	380	0.37	0.12	90	2.6	0.1	56	20	120	AS7-5725a
M-07-60	X14435	380	382	0.25	0.13	70	1.7	0.1	48	10	131	AS7-5725a
M-07-60	X14436	382	384	0.19	0.10	71	1.5	0.1	46	40	115	AS7-5725a
M-07-60	X14437	384	385.5	0.40	0.14	60	1.6	0.1	36	20	72	AS7-5725a
M-07-60	X14438	385.5	387	0.31	0.14	108	1.7	0.1	36	0.1	73	AS7-5725a
M-07-60	X14439	387	388.6	0.50	0.18	260	2.3	5	26	0.1	30	AS7-5725a

APPENDIX 3

CERTIFICATES OF ANALYSIS

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5418

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

23-Jul-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07002
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G32786	0.45	0.013
2	G32787	0.24	0.007
3	G32788	0.20	0.006
4	G32789	0.21	0.006
5	G32790	0.27	0.008
6	G32791	0.29	0.008
7	G32792	0.40	0.012
8	G32793	0.75	0.022
9	G32794	0.62	0.018
10	G32795	0.21	0.006
11	G32796	0.55	0.016
12	G32797	0.80	0.023
13	G32798	0.71	0.021
14	G32799	0.90	0.026
15	G32800	<0.03	<0.001
16	G32801	0.70	0.020
17	G32802	0.73	0.021
18	G32803	0.73	0.021
19	G32804	0.56	0.016
20	G32805	0.62	0.018
21	G32806	0.73	0.021
22	G32807	1.00	0.029
23	G32808	0.86	0.025
24	G32809	0.89	0.026
25	G32810	0.63	0.018

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5418 23-Jul-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	G32811	0.61	0.018
27	G32812	0.77	0.022
28	G32813	0.91	0.027
29	G32814	0.54	0.016
30	G32815	0.55	0.016
31	G32816	0.54	0.016
32	G32817	0.77	0.022
33	G32818	1.07	0.031
34	G32819	0.78	0.023
35	G32820	0.77	0.022
QC DATA:			
Repeat:			
1	G32786	0.41	0.012
7	G32792	0.40	0.012
8	G32793	0.75	0.022
10	G32795	0.21	0.006
12	G32797	0.80	0.023
14	G32799	0.91	0.027
17	G32802	0.74	0.022
19	G32804	0.54	0.016
24	G32809	0.93	0.027
28	G32813	0.91	0.027
33	G32818	1.07	0.031
Resplit:			
1	G32786	0.44	0.013
Standard:			
S125		1.79	0.052

JJ/bp
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

23-Jul-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5418

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07002
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G32786	2.1	0.75	<5	40	<5	0.33	2	10	70	1974	4.28	<10	0.49	299	17	<0.01	5	780	46	5	<20	13	0.02	<10	13	<10	<1	99
2	G32787	3.2	0.23	<5	40	<5	0.20	3	11	68	3498	6.33	<10	<0.01	39	10	0.01	6	570	20	<5	<20	13	0.02	<10	7	<10	<1	57
3	G32788	3.6	0.19	<5	45	<5	0.42	1	14	76	4481	5.39	<10	0.03	556	8	0.01	5	370	28	<5	<20	19	0.01	<10	4	<10	<1	21
4	G32789	2.4	0.18	<5	55	<5	0.30	4	28	64	1810	8.15	<10	<0.01	274	13	<0.01	7	540	48	<5	<20	21	0.04	<10	4	<10	<1	69
5	G32790	2.3	0.20	<5	45	<5	0.21	4	31	76	2396	7.02	<10	<0.01	107	13	0.01	7	610	40	<5	<20	16	0.03	<10	5	<10	<1	88
6	G32791	2.9	0.22	<5	35	<5	0.22	3	9	74	3193	3.76	<10	<0.01	63	10	0.01	5	660	40	<5	<20	14	<0.01	<10	6	<10	1	74
7	G32792	2.3	0.45	<5	35	<5	0.29	1	14	96	2813	3.77	<10	0.24	181	16	0.01	5	770	26	<5	<20	13	0.01	<10	9	<10	1	43
8	G32793	2.5	0.83	15	35	<5	0.92	1	11	57	2492	3.92	<10	0.79	945	19	0.01	5	770	22	10	<20	35	0.02	<10	16	<10	3	71
9	G32794	2.2	0.32	<5	25	<5	0.59	1	14	60	2899	3.62	<10	0.24	529	11	0.01	4	630	20	<5	<20	28	0.01	<10	8	<10	2	27
10	G32795	2.3	0.20	40	35	<5	0.21	4	10	69	1725	3.83	<10	<0.01	26	13	0.01	5	780	52	15	<20	15	0.02	<10	4	<10	<1	183
11	G32796	2.0	0.22	<5	30	<5	1.30	4	12	71	2254	3.74	<10	0.13	425	16	0.01	13	690	32	30	<20	81	<0.01	<10	7	<10	2	43
12	G32797	2.5	0.27	15	20	<5	1.55	1	10	79	2981	3.59	<10	0.17	516	27	0.01	3	550	30	<5	<20	96	0.03	<10	6	<10	1	72
13	G32798	2.3	0.43	<5	30	<5	1.45	2	11	64	2553	3.28	<10	0.27	501	10	0.02	3	700	22	<5	<20	93	0.02	<10	9	<10	3	67
14	G32799	2.7	0.61	<5	45	<5	0.86	2	11	80	2563	4.28	<10	0.35	471	14	0.01	7	610	24	10	<20	34	0.03	<10	9	<10	2	53
15	G32800	<0.2	0.97	10	265	15	0.52	<1	6	80	6	2.09	<10	0.63	525	2	0.09	6	790	18	<5	<20	78	0.13	<10	47	<10	4	47
16	G32801	3.2	0.49	<5	35	<5	1.40	2	14	75	3336	4.83	<10	0.27	737	12	<0.01	6	600	30	<5	<20	48	0.03	<10	9	<10	1	43
17	G32802	3.4	0.23	<5	25	<5	1.12	2	13	85	3847	4.00	<10	0.12	446	10	0.01	6	370	36	<5	<20	104	<0.01	<10	6	<10	<1	30
18	G32803	3.0	0.62	10	40	<5	1.52	<1	8	67	2269	3.14	<10	0.39	675	12	<0.01	5	670	22	<5	<20	55	0.02	<10	10	<10	3	78
19	G32804	2.6	0.49	<5	30	<5	1.32	1	9	57	2666	3.74	<10	0.39	525	10	0.02	4	650	32	<5	<20	160	0.02	<10	12	<10	2	68
20	G32805	2.9	0.33	<5	25	<5	0.87	2	12	69	2555	4.35	<10	0.14	443	10	<0.01	4	580	64	<5	<20	39	0.02	<10	8	<10	<1	109
21	G32806	6.3	0.19	30	25	<5	0.28	3	10	107	3140	4.57	<10	<0.01	128	10	0.01	6	430	68	10	<20	24	0.02	<10	6	<10	<1	105
22	G32807	3.9	1.13	60	60	<5	0.71	7	17	56	3372	3.85	20	0.58	271	223	0.03	24	330	142	80	<20	37	<0.01	<10	47	<10	7	167
23	G32808	5.2	0.35	30	25	<5	0.38	3	11	95	3318	4.87	<10	0.16	273	8	<0.01	4	480	86	<5	<20	14	0.04	<10	7	<10	<1	213
24	G32809	3.6	0.22	<5	20	<5	1.57	2	12	78	3559	3.88	<10	0.14	744	7	0.01	5	510	38	<5	<20	82	0.02	<10	7	<10	<1	117
25	G32810	4.2	0.20	5	30	<5	1.21	3	14	90	3575	5.17	<10	0.16	556	11	0.01	7	480	34	15	<20	67	0.02	<10	8	<10	<1	97

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007- 5418 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G32811	3.0	0.23	<5	30	<5	2.27	2	14	57	2730	4.24	<10	0.29	886	14	0.01	6	610	36	<5	<20	102	0.02	<10	10	<10	2	42
27	G32812	2.8	0.23	<5	30	<5	1.92	1	10	51	2784	3.33	<10	0.36	771	14	0.01	3	710	22	<5	<20	76	0.02	<10	9	<10	2	28
28	G32813	3.0	0.24	<5	25	<5	1.18	2	12	71	3590	3.60	<10	0.22	520	11	0.01	4	540	26	<5	<20	60	0.02	<10	9	<10	2	39
29	G32814	2.7	0.20	<5	25	<5	0.63	1	11	81	3055	3.88	<10	0.07	297	12	<0.01	5	530	36	<5	<20	54	0.02	<10	7	<10	1	38
30	G32815	3.1	0.39	20	30	<5	0.31	2	16	76	2611	4.54	<10	0.17	157	20	<0.01	6	730	28	15	<20	17	0.02	<10	12	<10	<1	51
31	G32816	1.7	0.34	<5	35	<5	1.47	<1	9	69	2165	2.92	<10	0.14	481	15	0.01	3	710	22	<5	<20	90	0.02	<10	8	<10	2	23
32	G32817	2.2	0.72	10	40	<5	1.18	<1	11	52	2642	3.73	<10	0.47	569	13	<0.01	3	790	18	<5	<20	60	0.02	<10	12	<10	3	56
33	G32818	3.4	0.30	<5	35	<5	0.44	2	12	68	3377	4.57	<10	0.09	205	14	<0.01	8	630	26	10	<20	27	<0.01	<10	7	<10	1	20
34	G32819	2.7	0.32	<5	40	<5	0.94	<1	10	77	2590	3.99	<10	0.18	720	12	<0.01	5	670	18	<5	<20	47	0.02	<10	7	<10	1	15
35	G32820	5.0	0.26	<5	35	<5	0.69	1	10	60	3524	4.48	<10	0.13	532	9	<0.01	4	630	28	<5	<20	39	0.02	<10	7	<10	1	16
QC DATA:																													
Repeat:																													
1	G32786	2.1	0.76	<5	45	<5	0.33	2	10	71	1961	4.25	<10	0.49	298	18	0.01	5	780	48	5	<20	16	0.02	<10	13	<10	1	100
10	G32795	2.3	0.21	50	30	<5	0.22	3	10	71	1718	3.90	<10	<0.01	27	13	0.01	4	780	54	15	<20	13	0.02	<10	5	<10	<1	178
19	G32804	2.5	0.52	<5	30	<5	1.35	2	9	60	2660	3.84	<10	0.41	535	13	0.02	4	650	32	5	<20	171	0.02	<10	12	<10	2	65
Resplit:																													
1	G32786	2.2	0.69	5	45	<5	0.37	2	11	68	2046	4.15	<10	0.45	308	20	<0.01	7	750	54	10	<20	20	0.02	<10	13	<10	2	95
Standard:																													
Pb113		11.5	0.27	55	65	<5	1.66	42	3	5	2294	1.05	<10	0.12	1438	81	0.02	3	70	5598	10	<20	63	0.01	<10	8	10	<1	6908

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl/bp
df/5418/5418r
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 5419

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

23-Jul-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07001
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G32751	0.82	0.024
2	G32752	0.79	0.023
3	G32753	0.60	0.017
4	G32754	0.81	0.024
5	G32755	0.84	0.024
6	G32756	0.50	0.015
7	G32757	0.79	0.023
8	G32758	0.71	0.021
9	G32759	0.82	0.024
10	G32760	<0.03	<0.001
11	G32761	0.60	0.017
12	G32762	0.66	0.019
13	G32763	0.72	0.021
14	G32764	0.58	0.017
15	G32765	0.28	0.008
16	G32766	0.47	0.014
17	G32767	0.66	0.019
18	G32768	0.65	0.019
19	G32769	0.48	0.014
20	G32770	0.59	0.017
21	G32771	0.67	0.020
22	G32772	0.61	0.018
23	G32773	0.90	0.026
24	G32774	0.69	0.020
25	G32775	0.83	0.024

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5419 23-Jul-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	G32776	1.12	0.033
27	G32777	0.68	0.020
28	G32778	0.76	0.022
29	G32779	0.77	0.022
30	G32780	0.38	0.011
31	G32781	0.67	0.020
32	G32782	0.64	0.019
33	G32783	0.43	0.013
34	G32784	0.79	0.023
35	G32785	0.46	0.013
QC DATA:			
Repeat:			
1	G32751	0.82	0.024
2	G32752	0.83	0.024
7	G32757	0.79	0.023
9	G32759	0.76	0.022
10	G32760	<0.03	<0.001
15	G32765	0.30	0.009
18	G32768	0.64	0.019
19	G32769	0.46	0.013
20	G32770	0.62	0.018
23	G32773	0.86	0.025
26	G32776	1.17	0.034
31	G32781	0.72	0.021
34	G32784	0.82	0.024
Resplit:			
1	G32751	0.83	0.024
Standard:			
SJ32		2.63	0.077

JJ/bp
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

19-Jul-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5419

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07001
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G32751	3.4	0.57	20	20	<5	1.29	<1	11	89	3612	5.18	<10	0.40	872	8	0.02	2	1140	38	<5	<20	35	<0.01	<10	11	<10	3	44
2	G32752	3.6	0.93	20	30	<5	1.08	<1	11	75	2575	4.29	<10	0.69	597	18	0.02	2	1330	34	<5	<20	50	<0.01	<10	23	<10	4	57
3	G32753	2.5	0.89	20	50	<5	0.93	<1	10	63	1630	3.62	<10	0.66	666	18	0.02	3	1410	32	<5	<20	64	<0.01	<10	26	<10	4	83
4	G32754	3.4	0.73	25	20	<5	1.27	<1	11	92	2674	4.63	<10	0.54	747	11	0.02	3	1160	54	<5	<20	38	<0.01	<10	16	<10	4	77
5	G32755	2.9	0.70	20	25	<5	1.09	<1	10	56	2601	3.72	<10	0.53	658	20	0.02	2	1360	30	<5	<20	38	<0.01	<10	16	<10	4	62
6	G32756	1.9	1.00	15	50	<5	1.36	<1	9	48	1551	3.58	<10	0.78	776	22	0.02	3	1660	24	<5	<20	57	<0.01	<10	25	<10	5	103
7	G32757	2.9	0.87	15	40	<5	1.29	<1	9	41	2188	3.21	<10	0.72	778	24	0.02	2	1540	24	<5	<20	56	<0.01	<10	26	<10	5	73
8	G32758	2.6	0.93	15	35	<5	0.80	<1	10	44	1953	3.44	<10	0.77	664	26	0.02	2	1540	48	<5	<20	40	<0.01	<10	21	<10	5	119
9	G32759	3.1	0.99	15	30	<5	1.24	<1	10	40	1793	4.05	<10	0.89	829	28	0.02	2	1590	92	<5	<20	38	<0.01	<10	21	<10	5	90
10	G32760	0.7	1.00	10	240	<5	0.65	<1	6	77	10	2.22	<10	0.59	572	1	0.08	6	960	8	<5	<20	82	0.14	<10	38	<10	4	46
11	G32761	2.7	1.02	15	45	<5	0.63	<1	9	52	2254	3.55	<10	0.83	559	29	0.02	2	1560	22	<5	<20	35	<0.01	<10	21	<10	4	72
12	G32762	2.7	0.95	15	35	<5	0.59	<1	10	61	2590	3.73	<10	0.74	490	23	0.01	3	1420	20	<5	<20	34	<0.01	<10	18	<10	4	57
13	G32763	4.1	0.89	15	25	<5	0.51	<1	11	81	3877	3.97	<10	0.71	528	20	0.02	2	1300	26	<5	<20	39	<0.01	<10	17	<10	3	54
14	G32764	2.9	0.79	15	25	<5	0.66	<1	14	51	2619	4.21	<10	0.62	466	23	0.02	2	1430	24	<5	<20	38	<0.01	<10	17	<10	4	43
15	G32765	3.2	1.18	35	45	<5	0.99	2	19	57	2709	3.60	20	0.63	200	196	0.04	13	620	54	10	<20	64	0.04	<10	40	<10	9	277
16	G32766	2.3	1.06	15	55	<5	1.13	<1	10	74	1670	3.88	<10	0.88	777	25	0.02	3	1440	24	<5	<20	54	<0.01	<10	23	<10	4	74
17	G32767	2.6	0.98	15	30	<5	1.48	<1	12	74	1988	3.65	<10	0.82	1033	17	0.02	3	1350	34	<5	<20	51	<0.01	<10	20	<10	4	77
18	G32768	2.7	0.94	15	60	<5	1.61	<1	10	42	2013	3.86	<10	0.81	892	15	0.02	2	1520	38	<5	<20	64	<0.01	<10	29	<10	5	101
19	G32769	2.5	0.91	15	40	<5	2.09	<1	9	62	2148	3.77	<10	0.82	973	13	0.02	2	1370	26	<5	<20	86	<0.01	<10	21	<10	4	68
20	G32770	7.5	0.54	25	25	<5	1.20	1	11	55	2819	4.03	<10	0.42	621	15	0.01	2	1400	40	10	<20	31	<0.01	<10	12	<10	4	52
21	G32771	3.6	0.94	25	30	<5	1.09	<1	11	55	1929	3.86	<10	0.69	559	16	0.01	3	1570	28	<5	<20	29	<0.01	<10	15	<10	4	93
22	G32772	4.9	0.76	20	30	<5	1.22	<1	10	57	2197	3.76	<10	0.64	769	17	0.01	2	1360	20	<5	<20	31	<0.01	<10	14	<10	4	74
23	G32773	7.2	0.54	25	25	<5	1.08	<1	13	81	3285	5.47	<10	0.52	739	13	0.01	2	1270	68	5	<20	33	<0.01	<10	12	<10	4	88
24	G32774	2.6	1.02	20	35	<5	2.23	<1	8	52	1798	3.38	<10	1.28	1615	19	0.01	2	1530	20	<5	<20	146	<0.01	<10	15	<10	6	113
25	G32775	3.3	0.42	30	20	<5	1.68	<1	11	69	2674	4.41	<10	0.41	682	6	0.01	2	1280	34	<5	<20	89	<0.01	<10	10	<10	5	43

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007- 5419 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G32776	2.7	0.69	20	20	<5	0.87	<1	11	66	2580	4.20	<10	0.67	655	7	0.01	2	1450	44	<5	<20	42	<0.01	<10	16	<10	4	62
27	G32777	2.3	1.23	15	25	<5	1.20	<1	11	51	1659	4.20	<10	1.11	955	14	0.02	2	1560	38	<5	<20	98	<0.01	<10	27	<10	5	80
28	G32778	3.7	0.94	15	25	<5	1.11	<1	9	81	2799	4.59	<10	0.75	808	12	0.02	2	1280	58	<5	<20	73	<0.01	<10	16	<10	4	96
29	G32779	2.0	1.04	20	40	<5	1.01	1	9	45	1694	4.11	<10	0.84	1717	16	0.01	<1	1210	46	<5	<20	31	<0.01	<10	8	<10	4	181
30	G32780	5.9	0.28	30	25	<5	0.39	5	9	60	4021	5.91	<10	0.07	337	6	0.01	<1	1100	104	10	<20	14	<0.01	<10	4	<10	3	396
31	G32781	14.6	0.36	25	25	<5	0.28	5	11	83	5481	6.82	<10	0.10	200	8	0.01	<1	1100	102	5	<20	12	<0.01	<10	5	<10	3	319
32	G32782	2.5	0.89	25	45	<5	0.29	<1	8	63	2022	4.08	<10	0.50	519	15	0.01	1	1200	30	<5	<20	12	<0.01	<10	9	<10	4	112
33	G32783	3.7	0.40	15	35	<5	0.29	3	9	86	3586	3.96	<10	0.13	194	13	0.01	2	1050	38	<5	<20	13	<0.01	<10	6	<10	3	182
34	G32784	2.4	1.04	15	30	<5	1.95	<1	8	55	2101	4.37	<10	0.73	664	10	0.02	<1	990	24	<5	<20	116	<0.01	<10	14	<10	5	83
35	G32785	2.3	0.83	15	25	<5	2.34	<1	8	67	1861	4.16	<10	0.61	865	9	0.02	1	1010	38	<5	<20	108	<0.01	<10	12	<10	5	76
QC DATA:																													
Repeat:																													
1	G32751	3.6	0.55	20	20	<5	1.41	<1	11	86	3601	5.20	<10	0.40	870	9	0.02	2	1150	36	<5	<20	34	<0.01	<10	10	<10	3	35
19	G32769	2.4	0.89	15	35	<5	1.95	<1	9	60	2092	3.65	<10	0.80	961	12	0.02	2	1380	26	<5	<20	81	<0.01	<10	20	<10	4	66
Resplit:																													
1	G32751	3.5	0.52	20	20	<5	1.39	<1	10	85	3570	4.91	<10	0.39	877	9	0.02	2	1150	32	<5	<20	37	<0.01	<10	9	<10	3	33
Standard:																													
Pb113		11.2	0.27	55	60	<5	1.74	39	2	2	2335	1.08	<10	0.11	1489	55	0.02	1	70	5468	<5	<20	74	<0.01	<10	5	<10	1	6964

Aqua Regia Digestion
ICP Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/n930
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007-5423

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

23-Jul-07

No. of samples received: 35
Sample Type: Core
Project #: KSM
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)		
1	G32821	0.54	0.016		
2	G32822	1.05	0.031		
3	G32823	1.79	0.052		
4	G32824	1.06	0.031		
5	G32825	1.03	0.030		
6	G32826	1.06	0.031		
7	G32827	0.77	0.022		
8	G32828	0.74	0.022		
9	G32829	0.85	0.025		
10	G32830	0.87	0.025		
11	G32831	1.06	0.031		
12	G32832	1.08	0.031		
13	G32833	0.83	0.024		
14	G32834	0.73	0.021	47.9	1.397
15	G32835	0.62	0.018		
16	G32836	1.07	0.031		
17	G32837	1.15	0.034		
18	G32838	1.07	0.031		
19	G32839	1.38	0.040		
20	G32840	4.40	0.128		
21	G32841	<0.03	<0.001		
22	G32842	1.64	0.048		
23	G32843	2.80	0.082		
24	G32844	3.10	0.090		
25	G32845	1.04	0.030		
26	G32846	1.16	0.034		
27	G32847	1.07	0.031		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5423 23-Jul-07

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
28	G32848	1.35	0.039		
29	G32849	1.58	0.046		
30	G32850	1.00	0.029		
31	G32851	1.59	0.046		
32	G32852	1.73	0.050		
33	G32853	0.78	0.023		
34	G32854	1.18	0.034		
35	G32855	1.02	0.030		
QC DATA:					
Repeat:					
1	G32821	0.56	0.016		
9	G32829	0.90	0.026		
10	G32830	0.92	0.027		
12	G32832	1.12	0.033		
14	G32834			48.1	1.403
17	G32837	1.19	0.035		
19	G32839	1.34	0.039		
20	G32840	4.30	0.125		
24	G32844	3.20	0.093		
30	G32850	1.03	0.030		
34	G32854	1.18	0.034		
35	G32855	1.05	0.031		
Resplit:					
1	G32821	0.60	0.017		
35	G32855	1.10	0.032		
Standard:					
SI25		1.83			
SI25		1.80			
SJ32		2.63			

JJ/
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

23-Jul-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 2007- 5423

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 35
Sample Type: Core
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G32821	3.1	0.26	<5	30	<5	0.79	1	17	64	3352	4.61	<10	0.12	467	10	<0.01	5	640	42	<5	<20	48	0.02	<10	6	<10	2	9
2	G32822	2.7	0.72	<5	35	<5	0.97	<1	9	61	2901	3.51	<10	0.54	753	12	<0.01	4	750	16	<5	<20	56	0.04	<10	13	<10	3	55
3	G32823	4.0	1.16	40	50	<5	1.00	2	22	58	8685	4.15	20	0.67	204	608	0.05	64	<10	72	25	<20	60	0.02	<10	45	<10	7	81
4	G32824	2.5	0.85	5	30	<5	0.49	1	10	57	2672	3.96	<10	0.59	403	14	<0.01	5	800	24	<5	<20	29	0.02	<10	14	<10	2	81
5	G32825	2.6	0.90	20	35	<5	0.45	1	11	35	2753	3.99	<10	0.61	366	16	<0.01	3	780	24	5	<20	30	0.02	<10	15	<10	2	85
6	G32826	3.3	0.29	<5	25	<5	0.36	2	10	60	2928	4.32	<10	0.04	205	11	<0.01	4	680	32	<5	<20	22	0.02	<10	8	<10	1	15
7	G32827	2.8	0.25	5	35	<5	0.95	1	11	53	2747	3.54	<10	0.09	485	14	<0.01	4	740	44	<5	<20	48	0.02	<10	6	<10	2	36
8	G32828	2.9	0.39	<5	25	<5	1.87	2	9	59	2478	3.91	<10	0.23	724	12	<0.01	7	750	48	10	<20	95	0.01	20	9	<10	2	38
9	G32829	2.9	0.56	45	35	<5	0.44	<1	8	59	2333	3.15	<10	0.24	244	14	<0.01	4	700	18	<5	<20	21	0.02	<10	8	<10	2	34
10	G32830	3.4	0.67	5	40	<5	0.53	2	12	70	2599	4.00	<10	0.32	387	15	<0.01	5	760	28	5	<20	23	0.02	<10	10	<10	2	67
11	G32831	2.3	0.83	15	50	<5	1.81	1	8	39	2179	3.37	<10	0.67	954	15	<0.01	3	760	32	10	<20	94	0.03	<10	12	<10	3	51
12	G32832	3.7	0.34	25	35	<5	1.53	2	11	59	3227	3.65	<10	0.36	1105	10	<0.01	4	590	36	<5	<20	65	0.02	<10	9	<10	3	35
13	G32833	4.5	0.26	<5	35	<5	1.36	4	12	66	3304	4.56	<10	0.26	982	9	<0.01	6	640	52	<5	<20	68	0.03	<10	8	<10	2	106
14	G32834	>30	0.20	135	40	<5	0.37	6	10	85	4057	4.48	<10	0.03	276	10	0.01	5	260	202	325	<20	24	0.01	<10	8	<10	<1	238
15	G32835	18.6	0.21	75	40	<5	0.45	3	16	74	2451	5.22	<10	0.04	363	10	<0.01	5	610	66	135	<20	27	0.03	10	7	<10	<1	112
16	G32836	25.1	0.37	35	30	<5	0.52	4	12	98	3156	4.55	<10	0.27	457	12	<0.01	7	440	124	65	<20	28	0.02	<10	8	<10	<1	182
17	G32837	6.4	0.24	<5	30	<5	0.31	2	11	87	4215	4.18	<10	0.05	188	11	<0.01	4	510	32	<5	<20	21	<0.01	<10	6	<10	1	31
18	G32838	5.1	0.21	5	35	<5	0.21	2	11	101	2737	4.80	<10	<0.01	93	16	0.01	5	500	60	<5	<20	18	0.02	<10	7	<10	<1	64
19	G32839	5.0	0.65	<5	45	<5	0.49	2	13	96	3393	6.28	<10	0.36	451	11	<0.01	6	640	32	<5	<20	36	0.03	<10	11	<10	<1	40
20	G32840	10.9	0.41	55	40	<5	0.68	3	12	84	2754	4.81	<10	0.28	662	12	<0.01	6	670	122	20	<20	47	0.04	<10	7	<10	1	165
21	G32841	<0.2	1.06	10	280	15	0.57	<1	7	96	10	2.26	<10	0.68	557	2	0.10	6	860	20	<5	<20	90	0.14	<10	51	<10	6	49
22	G32842	5.3	0.22	35	40	<5	0.35	3	13	93	4178	5.49	<10	0.06	262	11	0.01	7	360	50	<5	<20	21	0.01	<10	7	<10	<1	47
23	G32843	3.9	0.41	15	40	<5	0.30	2	12	78	3109	5.08	<10	0.20	251	10	0.01	5	540	26	<5	<20	19	0.02	<10	8	<10	<1	42
24	G32844	9.4	0.20	60	35	<5	0.20	4	12	93	3127	5.27	<10	<0.01	58	10	0.01	6	480	52	<5	<20	18	0.02	10	6	<10	<1	144
25	G32845	3.0	0.49	30	35	<5	0.52	2	12	73	2295	4.56	<10	0.33	385	9	<0.01	5	710	38	5	<20	32	0.03	<10	8	<10	1	64

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G32846	3.0	0.59	15	40	<5	1.13	1	10	94	3037	4.02	<10	0.59	792	10	<0.01	6	560	32	<5	<20	69	0.03	<10	10	<10	2	50
27	G32847	4.9	0.29	<5	35	<5	1.52	3	12	78	3869	5.00	<10	0.42	859	10	0.01	4	460	132	<5	<20	122	0.02	<10	6	<10	2	23
28	G32848	3.0	0.52	<5	40	<5	1.02	2	12	89	2398	4.51	<10	0.44	618	15	0.01	5	690	48	<5	<20	65	0.03	<10	9	<10	1	49
29	G32849	3.0	0.41	20	40	<5	1.39	2	10	89	2904	3.89	<10	0.48	796	15	0.01	8	580	32	20	<20	89	<0.01	<10	10	<10	2	35
30	G32850	2.4	0.27	10	25	<5	1.34	2	8	79	2223	3.22	<10	0.29	631	11	<0.01	3	820	32	<5	<20	87	0.03	<10	8	<10	2	38
31	G32851	5.5	0.18	125	30	<5	0.27	4	11	92	3812	4.89	<10	<0.01	108	10	0.01	6	360	56	15	<20	21	0.01	<10	6	<10	<1	79
32	G32852	6.9	0.22	160	40	<5	0.56	5	8	91	2321	4.93	<10	0.08	342	12	0.01	6	700	58	25	<20	30	0.02	<10	8	<10	1	164
33	G32853	2.8	0.32	5	30	<5	1.81	4	10	72	2163	3.76	<10	0.49	819	11	0.01	5	740	80	<5	<20	125	0.03	<10	8	<10	3	95
34	G32854	3.2	0.33	5	30	<5	1.52	1	12	73	3186	3.70	<10	0.49	622	9	0.01	5	610	26	<5	<20	100	0.02	<10	9	<10	3	27
35	G32855	2.9	0.48	<5	50	<5	1.78	1	9	115	2740	3.48	<10	0.70	659	10	0.01	5	620	18	5	<20	116	0.02	<10	12	<10	3	42
QC DATA:																													
Repeat:																													
1	G32821	3.1	0.25	<5	30	<5	0.80	1	17	63	3488	4.65	<10	0.12	474	10	0.01	5	600	40	<5	<20	49	0.02	<10	6	<10	<1	9
10	G32830	3.6	0.68	10	40	<5	0.54	2	12	71	2658	4.06	<10	0.33	391	15	<0.01	7	750	26	15	<20	26	0.01	<10	10	<10	2	68
19	G32839	5.1	0.64	<5	45	<5	0.49	2	13	92	3386	6.30	<10	0.36	446	11	<0.01	7	650	36	<5	<20	36	0.03	<10	10	<10	<1	40
Resplit:																													
1	G32821	3.3	0.25	<5	35	<5	0.73	2	17	80	3476	5.17	<10	0.09	410	10	<0.01	7	630	50	5	<20	47	0.02	<10	6	<10	<1	9
Standard:																													
Pb113		10.9	0.27	60	65	<5	1.69	41	3	5	2387	1.07	<10	0.12	1458	75	0.02	4	60	5402	20	<20	71	<0.01	<10	8	10	<1	7103

Auqa Regia Digestion - ICP Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl/bp
df/5481S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 5424

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

24-Jul-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07004
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G32856	1.79	0.052
2	G32857	0.81	0.024
3	G32858	1.16	0.034
4	G32859	0.88	0.026
5	G32860	1.06	0.031
6	G32861	1.37	0.040
7	G32862	0.92	0.027
8	G32863	0.93	0.027
9	G32864	1.06	0.031
10	G32865	1.34	0.039
11	G32866	1.30	0.038
12	G32867	<0.03	<0.001
13	G32868	0.91	0.027
14	G32869	1.04	0.030
15	G32870	0.78	0.023
16	G32871	1.36	0.040
17	G32872	1.30	0.038
18	G32873	0.79	0.023
19	G32874	1.33	0.039
20	G32875	1.47	0.043
21	G32876	0.32	0.009
22	G32877	1.51	0.044
23	G32878	1.60	0.047
24	G32879	1.08	0.031

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7 - 5424

ET #.	Tag #	Au (g/t)	Au (oz/t)
25	G32880	1.83	0.053
26	G32881	1.21	0.035
27	G32882	0.94	0.027
28	G32883	0.88	0.026
29	G32884	1.58	0.046
30	G32885	1.83	0.053
31	G32886	1.13	0.033
32	G32887	0.86	0.025
33	G32888	1.37	0.040
34	G32889	0.92	0.027
35	G32890	2.84	0.083

QC DATA:

Repeat:

1	G32856	1.84	0.054
3	G32858	1.25	0.036
10	G32865	1.34	0.039
19	G32874	1.26	0.037
23	G32878	1.56	0.045
29	G32884	1.56	0.045
35	G32890	2.80	0.082

Resplits:

1	G32856	1.77	0.052

Standards:

SJ32		2.65	0.077

JJ/jl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

20-Jul-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5424

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07004
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G32856	6.5	0.37	20	45	<5	1.28	2	14	83	4939	5.02	<10	0.40	683	10	0.01	6	380	26	10	<20	74	<0.01	<10	8	<10	<1	33
2	G32857	3.9	0.21	<5	50	<5	1.41	3	13	95	3584	4.78	<10	0.31	741	22	0.01	6	390	44	5	<20	81	0.02	<10	8	<10	1	60
3	G32858	4.1	0.25	30	45	<5	1.29	2	12	102	3359	4.31	<10	0.29	807	12	0.01	8	520	36	15	<20	64	<0.01	<10	8	<10	2	36
4	G32859	2.8	0.37	<5	50	<5	1.58	2	13	89	2185	3.95	<10	0.37	647	15	0.01	6	770	64	5	<20	72	0.02	<10	9	<10	3	37
5	G32860	2.4	0.29	<5	40	<5	1.65	1	10	108	2156	3.78	<10	0.38	848	12	0.01	4	720	26	5	<20	69	0.03	<10	8	<10	3	28
6	G32861	5.4	0.25	45	35	<5	1.28	2	13	119	3440	4.48	<10	0.11	677	13	0.01	7	510	50	10	<20	55	0.01	<10	7	<10	<1	72
7	G32862	3.3	0.26	10	35	<5	1.73	1	12	100	2534	4.09	<10	0.28	742	12	0.01	5	680	30	<5	<20	98	0.02	<10	8	<10	2	35
8	G32863	5.5	0.23	60	40	<5	0.78	2	11	106	4034	4.93	<10	0.11	494	11	0.01	5	510	28	15	<20	27	0.01	<10	6	<10	<1	25
9	G32864	2.9	0.26	50	50	<5	0.82	2	13	84	2495	5.90	<10	0.12	599	10	<0.01	5	730	28	<5	<20	32	0.03	<10	7	<10	<1	31
10	G32865	4.3	0.25	85	45	<5	1.07	1	11	105	2192	4.40	<10	0.18	842	12	<0.01	5	750	34	10	<20	47	0.02	<10	7	<10	2	37
11	G32866	5.6	0.42	65	35	<5	0.64	1	11	94	2001	4.22	<10	0.20	344	11	0.01	6	720	34	10	<20	37	0.03	<10	8	<10	1	65
12	G32867	<0.2	1.00	15	240	15	0.56	<1	7	96	4	2.19	<10	0.60	540	3	0.10	5	870	20	<5	<20	82	0.12	<10	46	<10	3	43
13	G32868	3.3	0.58	10	30	<5	1.15	2	10	77	1822	4.37	<10	0.54	805	13	<0.01	5	810	22	5	<20	46	0.02	<10	9	<10	<1	48
14	G32869	2.8	1.01	<5	50	<5	0.97	2	9	86	2030	3.70	<10	0.84	656	17	0.01	7	780	22	20	<20	61	<0.01	<10	13	<10	2	59
15	G32870	2.5	0.87	10	55	<5	1.18	1	10	72	1747	3.66	<10	0.74	703	14	0.01	5	910	22	10	<20	75	0.02	<10	16	<10	3	51
16	G32871	3.9	0.81	<5	50	<5	1.79	<1	10	85	3051	3.61	<10	0.53	579	14	0.02	3	730	22	<5	<20	133	0.01	<10	16	<10	1	38
17	G32872	3.9	0.33	10	40	<5	0.72	3	16	91	2286	6.55	<10	0.11	310	15	0.01	7	580	58	<5	<20	48	0.03	<10	7	<10	<1	29
18	G32873	2.7	0.29	<5	20	<5	2.47	<1	13	107	2077	3.91	<10	0.14	644	17	0.02	4	750	16	<5	<20	859	0.02	<10	7	<10	2	12
19	G32874	2.6	0.39	5	35	<5	1.43	<1	13	97	2275	4.23	<10	0.22	457	14	0.02	3	730	28	<5	<20	245	0.03	<10	8	<10	2	18
20	G32875	4.1	0.29	20	10	<5	1.43	4	12	88	3170	5.29	<10	0.06	526	11	0.01	6	630	46	<5	<20	77	0.02	<10	8	<10	<1	133
21	G32876	3.2	1.23	45	55	<5	1.01	2	22	57	2702	3.58	20	0.68	202	209	0.04	10	410	60	15	<20	62	0.05	<10	49	<10	7	264
22	G32877	3.6	0.39	20	40	<5	0.49	2	11	107	3121	4.42	<10	0.18	346	11	0.01	4	630	44	<5	<20	40	0.02	<10	7	<10	<1	102
23	G32878	3.4	0.26	50	45	<5	0.55	2	13	109	3039	5.54	<10	<0.01	232	11	0.01	6	770	34	<5	<20	39	0.02	<10	7	<10	<1	47
24	G32879	3.1	0.25	40	45	<5	1.11	1	9	84	2338	4.55	<10	0.04	595	8	0.01	4	770	30	<5	<20	80	0.03	<10	5	<10	2	51
25	G32880	2.9	0.85	25	60	<5	1.12	1	11	98	2548	4.14	<10	0.45	595	15	0.01	7	730	20	15	<20	87	0.01	<10	11	<10	2	43

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007- 5424 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G32881	3.1	0.73	25	60	<5	1.12	1	12	82	2613	4.43	<10	0.52	782	10	0.01	3	780	28	<5	<20	73	0.02	<10	10	<10	2	42
27	G32882	2.8	0.30	30	45	<5	0.50	1	9	105	2174	4.57	<10	0.08	303	10	0.01	6	780	30	<5	<20	30	0.02	<10	7	<10	1	17
28	G32883	4.2	0.46	25	40	<5	0.22	1	11	99	3077	4.32	<10	0.20	135	12	0.01	3	590	24	<5	<20	20	0.02	<10	6	<10	<1	34
29	G32884	3.9	0.76	<5	35	<5	0.41	3	14	100	2948	4.33	<10	0.47	271	14	0.01	6	570	32	<5	<20	44	0.01	<10	10	<10	<1	58
30	G32885	3.8	0.80	<5	40	<5	0.27	18	11	98	2477	3.60	<10	0.52	233	16	0.01	4	640	82	5	<20	36	0.02	<10	10	<10	<1	724
31	G32886	4.9	0.22	<5	35	<5	0.17	2	11	123	3330	4.94	<10	<0.01	51	13	0.01	5	460	84	<5	<20	20	0.02	<10	7	<10	<1	134
32	G32887	2.7	0.23	<5	35	<5	0.20	3	14	109	2635	5.36	<10	<0.01	90	10	0.01	5	520	92	<5	<20	18	0.02	<10	8	<10	<1	103
33	G32888	1.9	0.75	<5	40	<5	0.67	1	9	109	1804	4.33	<10	0.47	430	17	0.01	5	700	40	<5	<20	62	0.02	<10	17	<10	<1	53
34	G32889	1.9	0.66	<5	40	<5	1.28	<1	9	119	1734	3.92	<10	0.43	624	11	0.01	4	670	18	<5	<20	128	0.03	<10	18	<10	<1	57
35	G32890	3.1	0.54	<5	35	<5	1.42	2	11	110	3052	4.75	<10	0.42	563	11	0.02	6	440	38	<5	<20	251	0.03	<10	21	<10	<1	45
QC DATA:																													
Repeat:																													
1	G32856	6.9	0.37	35	45	<5	1.32	2	15	83	4937	5.13	<10	0.39	697	9	0.01	6	450	28	10	<20	76	0.02	<10	7	<10	1	35
10	G32865	4.2	0.25	65	40	<5	1.09	1	11	107	2201	4.44	<10	0.19	859	11	<0.01	5	720	32	<5	<20	45	0.03	<10	7	<10	1	38
19	G32874	2.7	0.37	<5	40	<5	1.39	1	12	93	2197	4.14	<10	0.22	448	11	0.02	4	710	26	<5	<20	231	0.02	<10	8	<10	1	18
Resplit:																													
1	G32856	6.6	0.35	15	45	<5	1.26	3	13	87	4873	4.90	<10	0.40	657	11	0.01	12	380	28	25	<20	73	<0.01	<10	9	<10	<1	33
Standard:																													
Pb113		11.2	0.27	55	60	<5	1.74	39	2	2	2335	1.08	<10	0.11	1489	55	0.02	1	70	5468	<5	<20	74	<0.01	<10	5	<10	1	6964

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/AA-Finish

JJ/nl/jl
df/5416S
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 5425

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

24-Jul-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07005
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G32891	0.73	0.021
2	G32892	1.17	0.034
3	G32893	0.21	0.006
4	G32894	0.47	0.014
5	G32895	0.68	0.020
6	G32896	0.74	0.022
7	G32897	0.91	0.027
8	G32898	0.51	0.015
9	G32899	0.65	0.019
10	G32900	0.90	0.026
11	G32901	1.42	0.041
12	G32902	1.43	0.042
13	G32903	0.61	0.018
14	G32904	0.87	0.025
15	G32905	0.28	0.008
16	G32906	0.59	0.017
17	G32907	0.31	0.009
18	G32908	0.69	0.020
19	G32909	0.63	0.018
20	G32910	0.84	0.024
21	G32911	0.66	0.019
22	G32912	0.88	0.026
23	G32913	1.47	0.043
24	G32914	0.33	0.010
25	G32915	0.51	0.015

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5425 24-Jul-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	G32916	0.79	0.023
27	G32917	0.63	0.018
28	G32918	0.53	0.015
29	G32919	0.41	0.012
30	G32920	0.99	0.029
31	G32921	0.50	0.015
32	G32922	0.38	0.011
33	G32923	0.47	0.014
34	G32924	0.70	0.020
35	G32925	<0.03	<0.001

QC DATA:

Repeat:

1	G32891	0.81	0.024
2	G32892	1.10	0.032
6	G32896	0.79	0.023
7	G32897	0.94	0.027
10	G32900	0.91	0.027
11	G32901	1.48	0.043
12	G32902	1.53	0.045
16	G32906	0.57	0.017
19	G32909	0.67	0.020
22	G32912	0.94	0.027
23	G32913	1.48	0.043
26	G32916	0.85	0.025

Resplit:

1	G32891	0.68	0.020

Standard:

OXD 57	0.41	0.012
OXK48	3.48	0.101
SJ32	2.66	0.078

JJ/bp
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

20-Jul-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 2007- 5425

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07005
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G32891	2.7	0.37	<5	30	<5	0.88	4	12	123	2782	5.01	<10	0.27	494	14	0.02	6	280	56	<5	<20	98	0.02	<10	14	<10	<1	105
2	G32892	2.7	0.38	<5	35	<5	0.82	1	9	104	2811	4.81	<10	0.21	495	10	0.01	4	410	26	<5	<20	36	0.03	<10	14	<10	<1	36
3	G32893	3.8	0.18	<5	35	<5	0.57	2	16	115	3736	5.69	<10	0.01	319	15	0.01	5	210	50	<5	<20	41	0.02	<10	11	<10	<1	39
4	G32894	4.2	0.24	<5	50	<5	0.65	4	18	87	4388	6.65	<10	0.11	414	13	0.01	4	160	102	<5	<20	52	0.03	<10	13	<10	<1	139
5	G32895	5.4	0.33	<5	40	<5	0.88	2	18	84	3572	6.14	<10	0.15	411	12	0.01	7	310	56	<5	<20	64	0.02	<10	9	<10	<1	37
6	G32896	2.5	0.68	<5	40	<5	1.43	5	8	77	2077	3.39	<10	0.43	850	13	0.01	4	650	64	<5	<20	69	0.03	<10	13	<10	2	317
7	G32897	3.0	0.68	<5	40	<5	1.43	5	9	72	2577	3.58	<10	0.42	837	12	0.01	3	660	74	<5	<20	68	0.02	<10	12	<10	2	274
8	G32898	2.4	0.47	<5	35	<5	1.09	3	12	71	2216	4.50	<10	0.36	747	9	0.01	3	450	38	<5	<20	123	0.02	<10	15	<10	<1	68
9	G32899	2.3	0.71	<5	40	<5	1.14	1	8	68	1604	3.56	<10	0.46	602	21	0.01	3	590	36	<5	<20	65	0.03	<10	17	<10	<1	72
10	G32900	1.9	0.57	<5	25	<5	0.74	1	8	93	1508	4.07	<10	0.41	653	13	0.01	3	450	26	<5	<20	42	0.03	<10	15	<10	<1	65
11	G32901	3.0	0.73	<5	35	<5	0.57	2	10	106	2390	4.56	<10	0.58	646	18	0.01	9	370	30	20	<20	43	0.02	<10	20	<10	<1	48
12	G32902	4.7	0.27	<5	35	<5	0.38	1	13	139	4850	4.14	<10	0.15	338	9	0.01	5	<10	20	<5	<20	34	<0.01	<10	13	<10	<1	25
13	G32903	1.9	0.31	<5	35	<5	1.64	6	12	87	1536	4.20	<10	0.27	668	13	0.01	4	480	188	<5	<20	158	0.03	<10	10	<10	1	295
14	G32904	1.8	0.57	<5	45	<5	1.15	2	12	85	1697	5.18	<10	0.30	629	13	0.01	5	510	38	<5	<20	74	0.04	<10	12	<10	<1	68
15	G32905	4.7	0.23	<5	40	<5	1.03	6	14	110	3069	5.94	<10	0.06	545	20	0.01	4	320	236	<5	<20	86	0.04	<10	8	<10	<1	284
16	G32906	5.8	0.18	50	35	<5	0.41	4	16	110	2937	6.69	<10	0.01	242	26	0.01	7	310	94	45	<20	35	0.03	30	10	<10	<1	127
17	G32907	3.7	0.20	<5	40	<5	0.79	2	12	93	3902	5.48	<10	0.10	458	28	0.01	6	370	66	<5	<20	59	0.02	<10	9	<10	<1	120
18	G32908	3.1	0.28	<5	35	<5	0.83	2	14	92	3369	5.47	<10	0.17	451	22	0.01	5	330	26	<5	<20	53	0.02	<10	10	<10	<1	63
19	G32909	1.5	0.58	<5	50	<5	1.26	1	11	77	1524	3.79	<10	0.49	753	19	0.01	4	560	14	<5	<20	74	0.03	<10	16	<10	<1	60
20	G32910	3.1	0.28	<5	40	<5	1.88	2	12	83	3731	4.23	<10	0.34	691	65	0.02	3	390	40	<5	<20	290	0.02	<10	15	<10	2	90
21	G32911	1.6	0.35	<5	40	<5	1.71	2	9	104	2091	4.07	<10	0.46	676	22	0.01	4	570	22	<5	<20	176	0.03	<10	19	<10	1	69
22	G32912	3.3	0.43	10	30	<5	1.86	2	12	85	3489	4.60	<10	0.33	722	24	0.01	6	310	44	5	<20	419	0.02	<10	13	<10	1	94
23	G32913	3.7	0.29	<5	40	<5	0.92	3	13	122	3881	5.12	<10	0.23	541	15	0.01	5	160	38	<5	<20	49	0.02	<10	9	<10	<1	72
24	G32914	2.9	0.79	10	40	<5	0.73	<1	15	61	2077	3.97	<10	0.52	551	9	0.01	4	750	22	<5	<20	34	0.02	<10	12	<10	1	54
25	G32915	6.1	0.60	25	40	<5	0.54	2	12	92	2457	5.54	<10	0.39	457	19	0.01	8	480	34	10	<20	24	0.03	<10	13	<10	<1	51

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G32916	3.6	0.73	10	50	<5	1.47	<1	13	89	2383	3.64	<10	0.46	782	13	0.01	4	720	18	<5	<20	81	0.02	<10	13	<10	2	47
27	G32917	4.1	0.47	35	40	<5	1.28	2	10	89	2532	5.01	<10	0.39	865	12	0.01	6	610	34	<5	<20	61	0.02	<10	10	<10	<1	38
28	G32918	3.2	0.30	10	35	<5	0.39	2	13	89	2500	5.41	<10	0.08	215	14	0.01	5	300	28	<5	<20	26	0.02	<10	10	<10	<1	21
29	G32919	2.1	0.92	5	45	<5	1.03	2	10	60	1492	4.54	<10	0.59	727	13	0.01	5	660	26	<5	<20	57	0.04	<10	15	<10	2	64
30	G32920	3.6	1.12	60	70	<5	0.73	3	17	55	3316	3.86	20	0.53	275	209	0.04	13	350	120	35	<20	35	0.04	<10	44	<10	6	142
31	G32921	3.1	0.57	<5	35	<5	1.99	2	22	76	2046	4.84	<10	0.41	965	14	0.01	6	550	42	10	<20	95	0.02	<10	11	<10	<1	51
32	G32922	2.6	0.86	15	75	<5	1.58	1	10	57	1635	3.25	<10	0.67	1048	12	0.01	3	900	40	<5	<20	67	0.03	<10	16	<10	3	95
33	G32923	3.3	0.63	10	50	<5	2.07	4	12	101	2131	4.32	<10	0.67	1056	16	0.01	8	510	70	20	<20	86	0.02	<10	14	<10	2	98
34	G32924	4.9	0.28	20	50	<5	1.66	2	27	88	3815	5.19	<10	0.40	874	33	0.01	7	200	44	10	<20	74	0.04	<10	8	<10	2	45
35	G32925	<0.2	0.86	25	245	20	0.49	<1	7	54	11	2.03	<10	0.62	527	2	0.05	4	900	18	<5	<20	66	0.12	<10	45	<10	3	43
QC DATA:																													
Repeat:																													
1	G32891	2.7	0.35	<5	35	<5	0.89	4	12	120	2691	5.09	<10	0.26	500	13	0.02	5	330	58	<5	<20	92	0.03	<10	13	<10	<1	110
10	G32900	1.8	0.55	<5	40	<5	0.75	2	9	90	1479	4.10	<10	0.40	652	14	0.01	5	480	30	<5	<20	48	0.03	<10	15	<10	<1	68
19	G32909	1.5	0.59	10	40	<5	1.31	1	12	77	1592	3.88	<10	0.51	779	17	0.01	4	580	14	<5	<20	80	0.03	<10	16	<10	1	62
Resplit:																													
1	G32891	2.7	0.40	<5	35	<5	0.97	3	11	87	2513	4.81	<10	0.30	525	12	0.01	6	430	50	<5	<20	96	0.03	<10	14	<10	<1	109
Standard:																													
Pb113		11.1	0.26	65	55	<5	1.72	35	2	5	2362	1.07	<10	0.11	1463	81	0.02	3	70	5256	25	<20	139	0.01	<10	8	60	<1	6921

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5425S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5426

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

23-Jul-07

No. of samples received: 35
Sample Type: Core
Project #: KSM
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G32926	0.50	0.015
2	G32927	0.32	0.009
3	G32928	0.47	0.014
4	G32929	0.71	0.021
5	G32930	0.70	0.020
6	G32931	0.77	0.022
7	G32932	0.75	0.022
8	G32933	0.97	0.028
9	G32934	1.08	0.031
10	G32935	<0.03	<0.001
11	G32936	1.54	0.045
12	G32937	0.76	0.022
13	G32938	0.67	0.020
14	G32939	0.38	0.011
15	G32940	0.47	0.014
16	G32941	0.43	0.013
17	G32942	1.94	0.057
18	G32943	0.67	0.020
19	G32944	0.37	0.011
20	G32945	0.59	0.017
21	G32946	0.51	0.015
22	G32947	0.53	0.015
23	G32948	0.39	0.011
24	G32949	0.94	0.027
25	G32950	0.77	0.022

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5426 23-Jul-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	G32951	1.36	0.040
27	G32952	0.63	0.018
28	G32953	0.84	0.024
29	G32954	1.10	0.032
30	G32955	1.18	0.034
31	G32956	0.65	0.019
32	G32957	0.55	0.016
33	G32958	0.48	0.014
34	G32959	0.88	0.026
35	G32960	0.45	0.013
QC DATA:			
Repeat:			
1	G32926	0.50	0.015
8	G32933	1.02	0.030
9	G32934	1.15	0.034
11	G32936	1.57	0.046
19	G32944	0.42	0.012
24	G32949	1.10	0.032
25	G32950	0.86	0.025
26	G32951	1.39	0.041
29	G32954	1.26	0.037
30	G32955	1.25	0.036
34	G32959	0.91	0.027
Resplit:			
1	G32926	0.46	0.013
Standard:			
OXD57		0.42	0.012
OXK48		3.48	0.101
SJ32		2.66	0.078

JJ/bp
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

20-Jul-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5426
Revised

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07006
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G32926	11.8	0.25	<5	35	<5	1.06	6	9	87	3908	4.26	<10	0.23	788	15	0.01	4	270	162	<5	<20	46	0.02	<10	8	<10	<1	353
2	G32927	2.5	0.29	<5	45	<5	1.52	1	7	69	1906	2.84	<10	0.42	903	13	0.01	4	540	28	5	<20	412	0.02	<10	15	<10	2	38
3	G32928	3.6	0.20	<5	35	<5	1.46	3	15	85	2883	4.00	<10	0.24	675	29	0.01	5	270	44	<5	<20	86	0.02	<10	7	<10	1	81
4	G32929	8.7	0.58	10	40	<5	1.33	1	11	72	2569	4.18	<10	0.48	821	12	0.01	5	410	22	<5	<20	67	0.02	<10	12	<10	<1	42
5	G32930	2.8	0.94	<5	55	<5	1.13	1	12	77	2906	4.10	<10	0.53	613	13	0.01	4	340	18	<5	<20	76	0.02	<10	16	<10	<1	37
6	G32931	7.1	0.74	<5	40	<5	1.52	2	9	72	2810	4.31	<10	0.53	968	39	0.01	4	380	26	5	<20	90	0.02	<10	13	<10	1	39
7	G32932	7.9	0.66	<5	35	<5	1.10	2	11	75	4120	4.77	<10	0.62	924	16	0.01	4	250	34	<5	<20	72	0.02	<10	17	<10	<1	58
8	G32933	5.4	0.47	<5	45	<5	1.51	3	16	73	4080	5.48	<10	0.72	1289	19	0.01	10	270	30	20	<20	102	0.01	<10	17	<10	1	30
9	G32934	5.6	0.34	<5	40	<5	1.40	2	27	54	3534	5.33	<10	0.37	870	12	0.01	5	510	22	5	<20	93	0.03	<10	10	<10	2	16
10	G32935	<0.2	0.98	5	245	10	0.53	<1	6	65	8	2.06	<10	0.63	532	3	0.09	4	790	12	<5	<20	96	0.11	<10	45	<10	3	40
11	G32936	4.8	0.46	<5	35	<5	1.14	2	10	62	2430	4.48	<10	0.46	828	16	0.01	5	530	26	10	<20	77	0.02	<10	11	<10	1	36
12	G32937	6.4	0.49	<5	35	<5	0.59	2	14	70	2636	4.88	<10	0.33	394	14	0.01	5	390	24	5	<20	46	0.02	<10	12	<10	<1	32
13	G32938	3.4	0.80	<5	40	<5	0.84	1	9	76	2584	3.69	<10	0.74	657	15	0.01	4	440	20	<5	<20	61	0.02	<10	17	<10	2	47
14	G32939	2.6	1.03	<5	35	<5	0.98	2	10	43	1526	4.39	<10	0.87	722	19	0.01	3	650	26	5	<20	81	0.03	<10	22	<10	1	73
15	G32940	11.3	0.74	<5	40	<5	1.36	5	11	83	3340	4.57	<10	0.53	762	20	0.01	6	490	42	10	<20	106	0.02	<10	19	<10	<1	287
16	G32941	3.3	0.77	<5	35	<5	0.61	<1	8	75	2478	3.29	<10	0.52	423	11	0.01	3	590	16	<5	<20	50	0.04	<10	12	<10	2	54
17	G32942	4.1	1.09	10	50	<5	0.98	2	21	52	8555	3.96	10	0.66	200	557	0.05	56	<10	46	20	<20	58	<0.01	<10	43	<10	5	60
18	G32943	3.6	0.61	5	40	<5	0.57	4	12	86	3190	4.61	<10	0.32	368	22	0.01	5	390	48	10	<20	49	0.03	<10	10	<10	<1	170
19	G32944	2.5	1.33	<5	70	<5	0.66	1	7	41	1353	3.77	<10	0.97	891	14	0.01	3	690	18	15	<20	51	0.03	<10	16	<10	2	79
20	G32945	10.7	0.58	<5	35	<5	0.20	2	11	89	3633	4.63	<10	0.29	188	23	0.02	4	460	28	<5	<20	16	0.02	<10	8	<10	<1	59
21	G32946	2.7	1.06	5	40	<5	0.28	1	9	46	2095	4.34	<10	0.58	372	13	0.02	4	680	22	<5	<20	18	0.02	<10	13	<10	2	65
22	G32947	3.2	1.27	5	65	<5	0.38	2	10	74	2677	4.44	<10	0.76	579	13	0.02	5	640	20	10	<20	26	0.02	<10	14	<10	2	74
23	G32948	2.8	1.22	20	55	<5	1.09	3	9	76	1766	4.45	<10	0.98	1253	18	0.02	5	680	40	10	<20	91	0.05	<10	17	<10	2	206
24	G32949	8.4	0.20	<5	35	<5	0.35	2	13	103	7070	5.17	<10	0.03	234	9	0.01	6	20	40	<5	<20	43	<0.01	<10	5	<10	<1	24
25	G32950	5.1	0.22	20	25	<5	0.15	1	11	97	4316	3.91	<10	<0.01	34	34	0.01	5	310	22	<5	<20	13	<0.01	<10	6	<10	<1	26

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007- 5426 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G32951	5.5	0.31	<5	30	<5	0.19	2	12	92	4490	3.77	<10	0.08	95	12	0.01	3	360	32	<5	<20	21	<0.01	<10	7	<10	1	54
27	G32952	4.1	0.88	<5	40	<5	0.74	2	10	81	2939	4.88	<10	0.70	594	14	0.02	4	520	26	10	<20	93	0.02	<10	21	<10	1	88
28	G32953	3.4	0.58	<5	35	<5	0.26	1	10	82	2889	4.47	<10	0.30	203	15	0.01	5	520	16	<5	<20	28	0.03	<10	11	<10	<1	44
29	G32954	5.5	0.53	<5	35	<5	0.25	2	11	87	5593	4.08	<10	0.31	266	16	0.01	7	290	24	10	<20	30	<0.01	<10	11	<10	<1	43
30	G32955	4.9	0.33	<5	35	<5	0.18	2	15	109	3826	5.23	<10	0.13	150	12	0.01	6	300	22	<5	<20	21	0.01	<10	9	<10	<1	21
31	G32956	5.6	0.76	<5	40	<5	0.33	1	11	83	2225	3.82	<10	0.57	370	14	0.01	5	580	36	5	<20	37	0.02	<10	13	<10	<1	78
32	G32957	5.9	0.45	<5	35	<5	0.36	5	11	87	2199	4.21	<10	0.29	400	14	0.02	4	580	42	<5	<20	36	0.02	<10	10	<10	<1	173
33	G32958	3.4	0.91	<5	40	<5	0.71	1	10	78	1924	3.88	<10	0.73	633	16	0.02	4	650	14	5	<20	97	0.02	<10	19	<10	2	51
34	G32959	2.8	0.81	<5	35	<5	0.67	1	11	98	2046	4.37	<10	0.65	462	17	0.02	6	550	24	<5	<20	79	0.02	<10	20	<10	1	42
35	G32960	2.1	1.06	<5	45	<5	0.83	2	9	65	1669	4.15	<10	0.88	554	13	0.02	5	780	16	10	<20	119	0.03	<10	24	<10	3	56
QC DATA:																													
Repeat:																													
1	G32926	11.5	0.26	<5	35	<5	1.09	6	9	91	3864	4.39	<10	0.23	811	15	0.01	6	310	174	<5	<20	47	0.03	<10	9	<10	<1	381
10	G32935	<0.2	0.96	<5	240	15	0.52	<1	6	63	7	2.01	<10	0.62	517	4	0.09	6	770	10	10	<20	97	0.09	<10	46	<10	4	37
19	G32944	2.6	1.37	<5	70	<5	0.68	1	7	42	1387	3.82	<10	0.99	908	15	0.01	3	700	18	10	<20	55	0.03	<10	17	<10	2	80
Resplit:																													
1	G32926	10.9	0.30	<5	35	<5	1.08	10	10	74	3698	4.51	<10	0.22	754	16	0.01	7	380	110	10	<20	45	0.01	<10	11	<10	<1	452
Standard:																													
Pb113		11.3	0.27	50	60	<5	1.63	33	2	5	2356	1.11	<10	0.11	1528	75	0.02	3	10	5418	14	<20	136	<0.01	<10	8	50	<1	6999

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl/bp
df/5425S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007- 5428

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

26-Jul-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07008
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	G36001	0.67	0.020		
2	G36002	0.99	0.029		
3	G36003	0.49	0.014		
4	G36004	0.54	0.016		
5	G36005	0.98	0.029		
6	G36006	0.49	0.014		
7	G36007	0.52	0.015		
8	G36008	0.52	0.015		
9	G36009	0.26	0.008		
10	G36010	1.47	0.043		
11	G36011	1.13	0.033		
12	G36012	0.76	0.022		
13	G36013	1.02	0.030		
14	G36014	0.58	0.017	72.1	2.103
15	G36015	0.64	0.019		
16	G36016	0.36	0.010		
17	G36017	0.26	0.008		
18	G36018	1.60	0.047		
19	G36019	0.34	0.010		
20	G36020	0.43	0.013		
21	G36021	0.56	0.016		
22	G36022	0.81	0.024		
23	G36023	0.76	0.022		
24	G36024	0.90	0.026		
25	G36025	0.47	0.014		
26	G36026	0.50	0.015		
27	G36027	0.67	0.020		
28	G36028	0.52	0.015		
29	G36029	0.79	0.023		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5428 26-Jul-07

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
30	G36030	0.75	0.022		
31	G36031	0.74	0.022		
32	G36032	1.22	0.036		
33	G36033	0.73	0.021		
34	G36034	0.74	0.022		
35	G36035	0.51	0.015		

QC DATA:

Repeat:					
1	G36001	0.66	0.019		
5	G36005	1.02	0.030		
6	G36006	0.56	0.016		
10	G36010	1.51	0.044		
11	G36011	1.15	0.034		
13	G36013	0.98	0.029		
14	G36014			73.5	2.143
19	G36019	0.36	0.010		
31	G36031	0.78	0.023		
32	G36032	1.17	0.034		
Repeat:					
1	G36001	0.67	0.020		
Standard:					
SJ32		2.66	0.078		
OXK48		3.48	0.101		
Cu120				34.3	1.000

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl/kc
XLS/07

20-Jul-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5428

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07008
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36001	3.9	0.12	<5	30	<5	0.37	2	12	116	3649	4.49	<10	<0.01	152	9	0.01	5	140	34	<5	<20	27	0.02	<10	6	<10	<1	88
2	G36002	3.3	0.20	<5	35	<5	0.71	5	10	87	2702	6.01	<10	0.13	362	10	0.01	7	260	60	<5	<20	49	0.02	<10	22	<10	<1	147
3	G36003	2.7	0.12	<5	30	<5	0.25	3	9	140	2535	4.03	<10	<0.01	138	11	0.01	5	170	32	<5	<20	33	0.02	<10	5	<10	<1	142
4	G36004	3.0	0.10	<5	30	<5	0.10	3	8	132	2718	3.61	<10	<0.01	66	14	0.01	7	30	20	<5	<20	17	<0.01	<10	5	<10	<1	71
5	G36005	2.4	0.19	<5	35	<5	0.68	2	9	136	2264	4.72	<10	0.03	339	10	0.01	7	380	18	<5	<20	57	0.02	<10	9	<10	<1	46
6	G36006	2.6	0.14	<5	25	<5	0.49	1	12	131	2084	4.16	<10	0.03	184	18	0.01	6	190	26	<5	<20	73	0.02	<10	7	<10	<1	45
7	G36007	6.5	0.13	25	25	<5	0.11	2	10	158	2988	4.61	<10	<0.01	44	15	0.01	8	110	32	10	<20	28	0.01	<10	6	<10	<1	34
8	G36008	3.8	0.05	<5	35	<5	0.12	2	6	187	3152	2.47	<10	<0.01	121	13	0.01	6	<10	28	<5	<20	11	<0.01	<10	3	<10	<1	94
9	G36009	4.1	0.09	<5	25	<5	0.28	2	7	162	2910	3.32	<10	<0.01	177	11	0.01	5	30	22	<5	<20	23	0.01	<10	5	<10	<1	89
10	G36010	2.7	0.19	<5	35	<5	0.57	2	10	132	1796	4.71	<10	0.06	359	12	0.01	6	190	20	<5	<20	36	0.03	<10	7	<10	<1	68
11	G36011	3.1	0.23	<5	40	<5	0.24	2	10	115	1930	5.19	<10	0.07	193	13	0.01	4	290	24	<5	<20	23	0.03	<10	7	<10	<1	62
12	G36012	3.8	0.21	<5	30	<5	0.14	1	10	146	2324	4.51	<10	0.02	90	15	0.01	5	310	18	<5	<20	17	0.02	<10	7	<10	<1	45
13	G36013	5.3	0.62	<5	40	<5	0.81	2	13	112	2509	5.72	<10	0.40	634	9	0.01	8	240	30	5	<20	50	0.02	<10	21	<10	<1	76
14	G36014	>30	0.46	75	30	<5	0.21	4	9	137	2274	4.52	<10	0.24	317	14	0.01	7	180	234	165	<20	18	0.02	<10	16	<10	<1	314
15	G36015	7.2	0.14	10	30	<5	0.10	2	10	128	2118	4.57	<10	<0.01	51	11	0.01	7	230	22	10	<20	18	0.01	<10	5	<10	<1	38
16	G36016	15.4	0.12	40	25	<5	0.09	2	8	132	2056	3.34	<10	<0.01	51	13	0.01	4	210	108	15	<20	30	0.02	<10	5	<10	<1	137
17	G36017	4.8	0.12	5	30	<5	0.09	2	10	119	2840	4.53	<10	<0.01	53	12	0.01	5	160	68	<5	<20	14	0.02	<10	4	<10	<1	142
18	G36018	0.4	0.60	2195	70	10	0.69	<1	28	22	41	4.74	10	2.03	761	5	0.14	97	1050	14	20	<20	56	0.08	<10	22	<10	9	52
19	G36019	5.2	0.16	10	35	<5	0.13	3	12	124	3171	5.31	<10	<0.01	54	12	0.01	7	270	44	<5	<20	16	0.02	<10	7	<10	<1	99
20	G36020	5.7	0.18	<5	30	<5	0.12	3	9	150	2489	4.24	<10	<0.01	59	13	0.01	6	260	58	<5	<20	19	0.02	<10	8	<10	<1	154
21	G36021	4.4	0.28	<5	35	<5	0.16	2	11	134	2325	4.62	<10	0.08	159	14	0.01	6	280	46	<5	<20	18	0.02	<10	9	<10	<1	63
22	G36022	13.6	0.16	55	30	<5	0.15	2	12	138	2058	5.07	<10	<0.01	56	10	0.01	7	440	46	10	<20	21	0.02	<10	6	<10	<1	73
23	G36023	6.3	0.38	15	35	<5	0.18	2	11	128	2566	5.31	<10	0.10	166	14	0.01	7	520	26	<5	<20	16	0.02	<10	11	<10	<1	79
24	G36024	9.6	0.40	<5	35	<5	0.13	4	10	143	2385	4.70	<10	0.12	176	13	0.01	8	370	46	5	<20	15	0.02	<10	14	<10	<1	220
25	G36025	4.2	0.15	<5	30	<5	0.09	1	10	199	2628	3.66	<10	<0.01	35	14	0.01	7	200	28	<5	<20	20	0.01	<10	6	<10	<1	25

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36026	3.5	0.18	<5	30	<5	0.14	2	10	115	2490	4.67	<10	<0.01	42	12	0.01	9	390	16	5	<20	17	<0.01	<10	7	<10	<1	26
27	G36027	3.8	0.17	<5	30	<5	0.12	2	11	141	2180	4.73	<10	<0.01	42	12	0.01	8	330	20	<5	<20	19	0.02	<10	7	<10	<1	55
28	G36028	8.7	0.27	45	30	<5	0.17	<1	9	111	1803	3.78	<10	0.04	67	10	0.01	4	540	34	10	<20	19	0.02	<10	5	<10	<1	42
29	G36029	4.0	0.71	<5	35	<5	0.35	1	11	88	1932	3.89	<10	0.44	268	15	0.01	6	740	20	<5	<20	33	0.02	<10	11	<10	2	54
30	G36030	3.9	0.78	10	30	<5	0.86	<1	10	68	2317	3.57	<10	0.68	822	14	0.01	3	630	62	5	<20	69	0.02	<10	10	<10	3	66
31	G36031	5.2	0.27	20	35	<5	0.19	2	13	87	2428	5.49	<10	0.02	59	13	0.01	6	500	44	5	<20	18	0.02	<10	6	<10	<1	34
32	G36032	3.5	0.70	<5	35	<5	0.25	2	12	73	2832	4.47	<10	0.37	229	13	0.01	5	600	18	<5	<20	23	0.01	<10	10	<10	<1	52
33	G36033	2.4	1.21	<5	45	<5	0.29	1	11	64	1699	4.24	<10	0.76	405	21	0.01	4	770	20	5	<20	28	0.03	<10	18	<10	1	79
34	G36034	3.3	0.53	<5	35	<5	0.25	1	12	73	2159	4.66	<10	0.26	170	17	0.02	5	660	34	<5	<20	25	0.02	<10	9	<10	<1	35
35	G36035	2.7	0.52	<5	35	<5	0.53	2	12	67	1371	4.63	<10	0.36	515	14	0.02	5	740	40	<5	<20	33	0.03	<10	11	<10	1	51
QC DATA:																													
Repeat:																													
1	G36001	3.7	0.11	<5	35	<5	0.37	2	12	112	3696	4.55	<10	<0.01	152	8	0.01	6	130	34	<5	<20	30	0.01	<10	6	<10	<1	86
10	G36010	2.7	0.18	<5	35	<5	0.57	2	9	126	1796	4.60	<10	0.06	357	11	0.01	6	180	20	<5	<20	34	0.03	<10	7	<10	<1	67
19	G36019	5.3	0.15	<5	30	<5	0.13	3	11	120	3136	5.21	<10	<0.01	54	12	0.01	8	280	42	5	<20	16	0.01	<10	7	<10	<1	100
Resplit:																													
1	G36001	4.0	0.12	<5	30	<5	0.37	3	13	129	3679	4.57	<10	<0.01	156	7	0.01	8	170	32	<5	<20	25	0.01	<10	7	<10	<1	99
Standard:																													
Pb113		22.8	0.25	45	55	<5	1.62	33	2	5	2357	1.01	<10	0.11	1413	76	0.02	3	70	5568	15	<20	69	<0.01	<10	7	10	<1	6912

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5425S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007- 5429

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

24-Jul-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07007
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	G32961	<0.03	<0.001		
2	G32962	0.43	0.013		
3	G32963	0.57	0.017		
4	G32964	1.16	0.034		
5	G32965	0.73	0.021		
6	G32966	0.77	0.022		
7	G32967	0.73	0.021		
8	G32968	0.52	0.015		
9	G32969	0.52	0.015		
10	G32970	0.41	0.012		
11	G32971	0.64	0.019		
12	G32972	0.64	0.019		
13	G32973	0.62	0.018		
14	G32974	0.72	0.021		
15	G32975	0.58	0.017		
16	G32976	0.53	0.015		
17	G32977	0.74	0.022		
18	G32978	0.78	0.023		
19	G32979	0.67	0.020		
20	G32980	0.58	0.017		
21	G32981	0.54	0.016		
22	G32982	0.57	0.017		
23	G32983	0.53	0.015		
24	G32984	0.41	0.012	112	3.266

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7 - 5429

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
25	G32985	0.47	0.014		
26	G32986	0.29	0.008		
27	G32987	0.51	0.015		
28	G32988	0.91	0.027		
29	G32989	0.67	0.020		
30	G32990	0.40	0.012		
31	G32991	0.44	0.013		
32	G32992	0.68	0.020	34.5	1.006
33	G32993	0.75	0.022		
34	G32994	0.47	0.014		
35	G32995	0.38	0.011		
QC DATA:					
Repeat:					
2	G32962	0.42	0.012		
4	G32964	1.11	0.032		
10	G32970	0.50	0.015		
19	G32979	0.77	0.022		
33	G32993	0.74	0.022		
Resplits:					
1	G32961	<0.03	<0.001		
Standard:					
SI25		1.82	0.053		
Pb113				22.7	0.662

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
XLS/07

24-Jul-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5429

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07007
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G32961	<0.2	0.99	<5	255	20	0.55	<1	6	98	4	2.18	<10	0.60	543	3	0.11	7	750	14	<5	<20	79	0.13	<10	46	<10	5	44
2	G32962	2.1	1.02	<5	70	<5	0.66	<1	9	81	1500	3.98	<10	0.84	503	10	0.03	4	720	20	<5	<20	77	0.02	<10	25	<10	2	79
3	G32963	2.3	1.01	<5	60	<5	1.02	1	8	63	1783	4.22	<10	0.81	592	58	0.02	4	620	18	<5	<20	124	0.02	<10	24	<10	3	66
4	G32964	3.2	0.39	<5	35	<5	0.58	<1	11	100	2606	4.24	<10	0.19	300	38	0.02	4	490	18	<5	<20	51	0.01	<10	8	<10	<1	21
5	G32965	4.1	0.64	<5	40	<5	1.41	1	10	91	2331	4.13	<10	0.43	722	27	0.02	5	620	14	<5	<20	159	0.02	<10	11	<10	3	40
6	G32966	5.2	0.41	<5	30	<5	1.61	1	12	87	3522	4.45	<10	0.40	865	16	0.02	5	370	22	<5	<20	164	0.02	<10	9	<10	3	22
7	G32967	2.7	0.94	<5	40	<5	1.14	<1	10	70	1783	4.21	<10	0.86	677	22	0.02	5	640	24	<5	<20	85	0.02	<10	17	<10	2	51
8	G32968	2.0	0.93	<5	55	<5	0.92	<1	10	70	1723	4.60	<10	0.77	551	42	0.03	4	660	16	<5	<20	72	0.02	<10	26	<10	2	48
9	G32969	2.0	0.90	<5	65	<5	0.81	<1	9	68	1579	4.29	<10	0.71	442	16	0.03	5	710	22	<5	<20	73	0.02	<10	24	<10	2	52
10	G32970	2.3	0.85	<5	85	<5	1.00	<1	9	76	1601	3.53	<10	0.66	531	19	0.02	4	740	16	<5	<20	96	0.02	<10	19	<10	2	58
11	G32971	5.1	0.85	<5	35	<5	1.21	2	12	51	2034	4.04	<10	0.72	663	16	0.02	5	640	18	10	<20	106	0.02	<10	14	<10	2	50
12	G32972	12.2	0.63	<5	40	<5	0.89	1	11	54	3387	4.59	<10	0.47	564	17	0.02	3	510	18	<5	<20	67	0.02	<10	11	<10	<1	37
13	G32973	4.8	0.84	<5	40	<5	1.58	1	11	59	1768	4.23	<10	0.67	821	13	0.02	4	580	16	<5	<20	152	0.02	<10	15	<10	<1	42
14	G32974	4.9	0.83	10	35	<5	1.07	<1	13	84	3051	4.25	<10	0.69	649	16	0.02	5	500	20	<5	<20	99	0.01	<10	15	<10	1	39
15	G32975	3.5	0.80	<5	35	<5	1.40	<1	11	55	1909	3.86	<10	0.64	737	24	0.02	3	690	16	<5	<20	131	0.02	<10	18	<10	2	41
16	G32976	3.2	0.82	5	40	<5	1.72	<1	9	55	1725	3.86	<10	0.69	860	23	0.02	4	740	16	<5	<20	167	0.02	<10	18	<10	3	45
17	G32977	5.5	0.60	<5	35	<5	1.27	1	12	62	2453	4.52	<10	0.55	832	14	0.02	4	610	24	<5	<20	104	0.02	<10	11	<10	2	29
18	G32978	3.5	0.95	<5	45	<5	0.68	1	10	54	2163	3.92	<10	0.83	566	14	0.02	4	720	18	5	<20	58	0.02	<10	16	<10	3	41
19	G32979	2.9	0.93	<5	40	<5	0.96	1	12	69	1798	4.21	<10	0.78	638	19	0.02	6	630	18	10	<20	113	0.02	<10	22	<10	2	39
20	G32980	3.5	0.95	<5	60	<5	0.81	<1	9	57	1566	4.00	<10	0.74	508	16	0.03	3	710	14	<5	<20	107	0.02	<10	26	<10	2	45
21	G32981	4.4	0.58	10	35	<5	0.42	<1	10	60	1513	4.08	<10	0.43	352	21	0.02	5	770	24	<5	<20	31	0.02	<10	11	<10	2	30
22	G32982	4.8	0.61	20	40	<5	0.27	2	10	87	1667	4.10	<10	0.43	225	21	0.02	8	730	28	15	<20	19	<0.01	<10	11	<10	2	45
23	G32983	3.6	0.55	20	30	<5	0.61	<1	11	52	1757	3.60	<10	0.41	434	19	0.02	3	700	18	<5	<20	40	0.02	<10	9	<10	3	30
24	G32984	>30	0.67	10	40	<5	0.51	2	10	52	1662	3.03	<10	0.53	394	21	0.02	3	780	108	<5	<20	43	0.01	<10	11	<10	3	107
25	G32985	6.5	0.90	<5	50	<5	0.98	<1	10	62	1412	3.72	<10	0.79	557	16	0.02	4	760	22	5	<20	114	0.02	<10	18	<10	3	51

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G32986	3.3	1.07	40	50	<5	1.00	2	21	53	2638	3.54	20	0.63	199	187	0.04	10	310	58	5	<20	49	0.04	<10	46	<10	6	279
27	G32987	3.1	0.90	10	55	<5	1.85	<1	11	56	1779	3.92	<10	0.78	726	19	0.03	3	680	18	<5	<20	246	0.02	<10	28	<10	3	55
28	G32988	13.5	0.60	20	35	<5	1.22	1	11	75	2806	3.94	<10	0.63	962	51	0.02	4	490	48	5	<20	87	0.02	<10	12	<10	3	63
29	G32989	4.8	0.98	20	50	<5	1.56	<1	12	77	2243	4.03	<10	0.89	864	17	0.02	4	640	18	5	<20	141	0.02	<10	21	<10	3	61
30	G32990	3.2	1.02	<5	120	<5	1.46	<1	10	51	1532	4.40	<10	0.90	812	16	0.03	4	710	22	<5	<20	136	0.03	<10	41	<10	3	76
31	G32991	3.1	0.98	<5	60	<5	1.80	<1	9	47	1337	3.85	<10	0.86	915	17	0.03	4	740	16	5	<20	135	0.02	<10	25	<10	3	50
32	G32992	>30	0.70	10	35	<5	0.98	7	11	60	2415	4.08	<10	0.64	672	123	0.02	4	590	176	10	<20	58	0.02	<10	14	<10	1	355
33	G32993	4.8	1.04	15	50	<5	1.65	1	10	49	1906	3.33	<10	0.92	996	164	0.02	5	680	46	10	<20	106	0.02	<10	18	<10	3	57
34	G32994	4.9	0.85	20	35	<5	1.22	2	11	65	1583	3.50	<10	0.79	898	18	0.02	4	640	1226	<5	<20	66	0.02	<10	14	<10	3	54
35	G32995	6.2	1.34	95	45	<5	1.90	2	20	48	881	4.99	<10	1.09	667	11	0.02	5	730	178	15	<20	72	0.05	<10	37	<10	4	75
QC DATA:																													
Repeat:																													
1	G32961	<0.2	1.00	15	255	<5	0.55	<1	7	99	6	2.23	<10	0.61	550	3	0.11	6	740	14	<5	<20	80	0.12	<10	47	<10	4	44
10	G32970	2.3	0.87	<5	75	<5	1.02	<1	9	76	1636	3.61	<10	0.68	545	19	0.03	4	770	18	<5	<20	97	0.02	<10	19	<10	3	60
19	G32979	3.0	0.94	<5	40	<5	0.99	1	12	71	1834	4.31	<10	0.80	656	17	0.03	5	660	18	<5	<20	114	0.02	<10	23	<10	2	40
Resplit:																													
1	G32961	<0.2	1.00	20	250	20	0.66	<1	7	106	6	2.24	<10	0.67	552	3	0.11	7	730	14	<5	<20	79	0.12	<10	47	<10	5	45
Standard:																													
Pb113		10.9	0.24	75	50	<5	1.72	38	2	5	2300	1.07	<10	0.10	1465	76	0.02	2	70	5482	15	<20	77	0.02	<10	8	10	<1	6953

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5429
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007-5430

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

24-Jul-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07009
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36036	0.76	0.022
2	G36037	0.65	0.019
3	G36038	0.56	0.016
4	G36039	0.84	0.024
5	G36040	0.76	0.022
6	G36041	0.89	0.026
7	G36042	0.51	0.015
8	G36043	0.55	0.016
9	G36044	2.41	0.070
10	G36045	0.84	0.024
11	G36046	0.71	0.021
12	G36047	1.11	0.032
13	G36048	0.91	0.027
14	G36049	0.75	0.022
15	G36050	0.75	0.022
16	G36051	0.65	0.019
17	G36052	1.32	0.038
18	G36053	0.65	0.019
19	G36054	1.02	0.030
20	G36055	1.55	0.045
21	G36056	0.93	0.027
22	G36057	0.96	0.028
23	G36058	1.41	0.041
24	G36059	0.72	0.021
25	G36060	0.67	0.020

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5430 24-Jul-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	G36061	0.69	0.020
27	G36062	0.75	0.022
28	G36063	0.57	0.017
29	G36064	<0.03	<0.001
30	G36065	0.59	0.017
31	G36066	0.70	0.020
32	G36067	0.75	0.022
33	G36068	0.55	0.016
34	G36069	0.91	0.027
35	G36070	2.17	0.063

QC DATA:

Repeat:

1	G36036	0.75	0.022
9	G36044	2.38	0.069
10	G36045	0.88	0.026
17	G36052	1.28	0.037
19	G36054	1.01	0.029
20	G36055	1.45	0.042
35	G36070	1.94	0.057

Resplit:

1	G36036	0.80	0.023

Standard:

SI25		1.82	0.053

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
XLS/07

24-Jul-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5430

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07009
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36036	4.1	0.92	10	40	<5	0.60	<1	10	62	2103	4.19	<10	0.72	536	31	0.01	5	690	22	<5	<20	42	0.02	<10	13	<10	2	87
2	G36037	4.7	0.40	10	35	<5	0.34	1	13	58	2477	5.06	<10	0.22	227	25	0.02	5	630	24	<5	<20	22	0.02	<10	6	<10	<1	40
3	G36038	6.5	0.23	<5	35	<5	0.23	2	13	73	1959	5.68	<10	0.04	87	32	0.02	5	620	34	<5	<20	16	0.02	<10	7	<10	<1	40
4	G36039	4.5	0.29	95	35	<5	0.37	<1	12	70	1384	4.39	<10	0.09	235	22	0.02	4	770	26	<5	<20	23	0.02	<10	7	<10	3	27
5	G36040	3.6	0.78	15	35	<5	0.99	<1	11	71	1962	5.13	<10	0.88	1318	18	0.02	5	640	28	<5	<20	63	0.03	<10	14	<10	2	88
6	G36041	3.5	0.49	<5	45	<5	0.66	2	16	69	2825	5.75	<10	0.41	779	23	0.02	5	570	30	<5	<20	44	0.02	<10	11	<10	1	45
7	G36042	2.6	0.74	5	35	<5	1.20	1	10	83	2303	3.86	<10	0.80	1024	22	0.02	5	630	32	<5	<20	83	0.02	<10	13	<10	3	63
8	G36043	2.9	0.83	<5	40	<5	0.36	2	12	68	2547	4.23	<10	0.59	364	25	0.02	6	590	30	5	<20	33	0.01	<10	15	<10	1	89
9	G36044	6.9	0.68	<5	45	<5	1.74	3	29	83	6566	7.54	<10	0.40	713	25	0.02	6	80	42	<5	<20	142	0.02	<10	34	<10	<1	69
10	G36045	2.8	1.03	<5	40	<5	0.69	1	15	61	2566	4.94	<10	0.90	560	30	0.02	5	490	26	<5	<20	52	0.02	<10	16	<10	<1	87
11	G36046	2.1	1.02	<5	45	<5	0.92	<1	11	74	2169	4.15	<10	0.94	780	63	0.02	4	700	24	<5	<20	62	0.02	<10	15	<10	2	73
12	G36047	4.2	0.87	<5	40	<5	0.97	2	14	61	3566	5.64	<10	0.55	564	31	0.02	4	520	18	<5	<20	96	0.02	<10	24	<10	1	58
13	G36048	3.5	1.13	5	55	<5	0.75	1	12	69	2965	4.67	<10	0.82	528	38	0.03	5	710	24	<5	<20	73	0.02	<10	25	<10	3	64
14	G36049	1.9	1.18	15	100	<5	0.72	<1	10	47	1518	4.19	<10	0.85	468	42	0.03	4	820	24	<5	<20	86	0.02	<10	29	<10	4	73
15	G36050	2.6	1.00	10	45	<5	0.66	<1	10	61	2277	3.54	<10	0.85	626	32	0.02	4	740	24	<5	<20	47	0.02	<10	17	<10	4	63
16	G36051	2.5	1.10	25	45	<5	0.53	<1	10	57	1779	3.46	<10	0.95	549	79	0.02	4	790	24	<5	<20	33	0.02	<10	15	<10	5	66
17	G36052	5.2	0.59	<5	35	<5	0.96	<1	14	77	5346	3.19	<10	0.46	564	34	0.02	4	370	24	<5	<20	76	<0.01	<10	12	<10	2	29
18	G36053	3.0	0.87	5	45	<5	0.27	<1	9	104	2186	3.69	<10	0.74	450	78	0.02	6	620	18	<5	<20	18	0.02	<10	21	<10	1	57
19	G36054	4.5	0.60	<5	35	<5	0.23	1	11	111	3142	3.99	<10	0.48	331	43	0.02	6	490	18	<5	<20	16	0.01	<10	16	<10	<1	42
20	G36055	5.1	0.57	35	35	<5	0.22	2	12	84	2211	4.52	<10	0.28	146	45	0.02	5	670	24	<5	<20	11	0.02	<10	12	<10	<1	71
21	G36056	3.2	1.17	15	45	<5	0.27	<1	11	108	2767	4.19	<10	0.91	408	50	0.02	6	620	24	<5	<20	21	0.02	<10	29	<10	<1	72
22	G36057	3.9	0.50	<5	35	<5	0.25	1	16	104	2604	5.16	<10	0.33	162	42	0.02	8	690	18	<5	<20	20	0.02	<10	13	<10	<1	36
23	G36058	4.1	0.79	20	40	<5	0.30	<1	9	99	2329	4.25	<10	0.61	277	51	0.02	6	810	22	<5	<20	20	0.02	<10	21	<10	1	64
24	G36059	2.7	1.05	30	35	<5	0.37	<1	13	89	1892	4.65	<10	0.94	497	27	0.02	7	800	36	<5	<20	28	0.02	<10	26	<10	<1	100
25	G36060	2.3	1.11	15	45	<5	0.33	<1	10	84	1973	4.27	<10	0.95	501	36	0.02	6	740	28	<5	<20	26	0.02	<10	27	<10	<1	91

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr		Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36061	2.9	1.34	<5	45	<5	0.29	<1	11	117	2093	4.49	<10	1.10	480	31	0.02	7	850	24	<5	<20	21	0.02	<10	29	<10	1	83
27	G36062	3.1	0.77	<5	35	<5	0.28	1	15	107	2261	4.56	<10	0.64	296	36	0.02	7	620	26	<5	<20	24	0.02	<10	20	<10	<1	68
28	G36063	3.2	1.14	25	45	<5	0.89	<1	13	102	1899	3.66	<10	0.99	707	34	0.02	7	760	20	5	<20	116	0.02	<10	25	<10	2	83
29	G36064	<0.2	0.94	<5	240	20	0.52	<1	6	90	7	2.11	<10	0.58	522	3	0.10	7	700	12	10	<20	75	0.11	<10	44	<10	4	42
30	G36065	4.4	0.64	<5	35	<5	0.35	1	12	79	3459	4.34	<10	0.55	479	27	0.02	6	570	26	<5	<20	20	0.01	<10	13	<10	1	40
31	G36066	3.5	1.16	10	45	<5	0.91	<1	13	60	1714	4.32	<10	0.96	663	55	0.02	6	870	26	<5	<20	95	0.02	<10	24	<10	4	88
32	G36067	2.4	1.03	10	50	<5	0.55	1	11	96	1927	4.11	<10	0.76	475	21	0.02	6	760	26	<5	<20	68	0.02	<10	24	<10	2	51
33	G36068	1.8	1.18	5	50	<5	0.76	<1	9	60	1498	4.14	<10	0.89	454	23	0.02	5	870	20	<5	<20	116	0.02	<10	32	<10	2	57
34	G36069	2.5	0.79	20	35	<5	0.77	<1	12	79	2220	3.68	<10	0.62	436	46	0.02	5	840	22	<5	<20	102	0.02	<10	20	<10	2	39
35	G36070	2.8	0.66	15	40	<5	0.51	<1	12	79	1860	4.24	<10	0.46	401	49	0.02	5	920	16	<5	<20	42	0.02	<10	12	<10	2	46
QC DATA:																													
Repeat:																													
1	G36036	4.2	0.94	<5	40	<5	0.62	<1	11	63	2158	4.32	<10	0.74	554	32	0.02	4	700	22	<5	<20	44	0.02	<10	13	<10	2	89
10	G36045	2.9	1.04	15	40	<5	0.69	2	15	61	2586	4.96	<10	0.91	562	31	0.02	7	500	26	5	<20	53	0.02	<10	16	<10	<1	88
19	G36054	4.4	0.60	10	35	<5	0.23	<1	11	112	3150	3.98	<10	0.48	333	54	0.02	6	500	18	<5	<20	18	0.01	<10	16	<10	<1	42
Resplit:																													
1	G36036	3.9	0.92	<5	40	<5	0.59	<1	11	73	2096	4.19	<10	0.71	526	19	0.02	5	720	22	<5	<20	42	0.02	<10	13	<10	3	86
Standard:																													
Pb113		11.5	0.27	55	65	<5	1.66	42	3	5	2294	1.05	<10	0.12	1438	81	0.02	3	70	5598	10	<20	63	0.01	<10	8	10	<1	6908

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
df/5429
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007-5431

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

2-Aug-07

No. of samples received: 35
Sample Type: Core
Project #: KSM
Shipment #: 07010
Submitted by:Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G32996	0.18	0.005
2	G32997	<0.03	<0.001
3	G32998	0.17	0.005
4	G32999	0.55	0.016
5	G33000	0.32	0.009
6	G34101	3.20	0.093
7	G34102	0.32	0.009
8	G34103	0.53	0.015
9	G34104	0.28	0.008
10	G34105	0.57	0.017
11	G34106	0.57	0.017
12	G34107	0.54	0.016
13	G34108	0.48	0.014
14	G34109	0.73	0.021
15	G34110	1.08	0.031
16	G34111	0.75	0.022
17	G34112	0.89	0.026
18	G34113	0.40	0.012
19	G34114	0.35	0.010
20	G34115	0.70	0.020
21	G34116	0.78	0.023
22	G34117	0.76	0.022
23	G34118	0.97	0.028
24	G34119	0.70	0.020
25	G34120	0.63	0.018
26	G34121	0.64	0.019
27	G34122	0.64	0.019

Seabridge Gold Inc. 2-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G34123	0.81	0.024
29	G34124	1.08	0.031
30	G34125	0.89	0.026
31	G34126	0.54	0.016
32	G34127	0.43	0.013
33	G34128	0.49	0.014
34	G34129	<0.03	<0.001
35	G34130	1.09	<0.001

QC DATA:

Repeat:

1	G32996	0.20	0.006
4	G32999	0.60	0.017
6	G34101	2.96	0.086
8	G34103	0.53	0.015
10	G34105	0.54	0.016
11	G34106	0.59	0.017
14	G34109	0.76	0.022
15	G34110	1.10	0.032
17	G34112	0.86	0.025
19	G34114	0.35	0.010
22	G34117	0.81	0.024
23	G34118	0.92	0.027
29	G34124	1.17	0.034
32	G34127	0.43	0.013
33	G34128	0.50	0.015

Resplits:

1	G32996	0.18	0.005

Standard:

SI25		1.80	0.052

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl/jl
XLS/07

26-Jul-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5431

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1


No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07010
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G32996	<0.2	2.76	30	485	<5	4.81	2	27	32	6	6.10	<10	2.59	1192	<1	0.03	1	1070	18	<5	<20	183	0.09	<10	107	<10	10	80
2	G32997	<0.2	2.97	35	415	<5	3.55	2	25	39	4	6.48	<10	2.98	896	<1	0.04	2	1000	16	<5	<20	142	0.11	<10	133	<10	10	79
3	G32998	1.8	2.28	30	105	<5	2.78	2	26	24	438	6.32	<10	1.93	977	22	0.02	<1	1210	22	<5	<20	109	0.08	<10	75	<10	10	86
4	G32999	3.7	1.11	20	80	<5	1.01	2	8	46	2676	3.33	<10	0.91	693	10	0.02	2	1030	20	<5	<20	67	<0.01	<10	14	<10	5	64
5	G33000	4.3	1.11	35	65	<5	1.54	1	7	60	1333	3.36	<10	1.00	1157	16	0.02	2	1010	16	<5	<20	109	<0.01	<10	14	<10	5	65
6	G34101	19.7	0.37	40	40	<5	0.89	3	7	67	1650	3.81	<10	0.24	521	17	0.01	2	950	84	<5	<20	62	<0.01	<10	4	<10	4	86
7	G34102	21.6	0.21	180	35	<5	0.29	3	11	92	1851	5.55	<10	0.02	100	10	0.02	<1	900	54	40	<20	17	<0.01	<10	4	<10	3	51
8	G34103	3.1	0.36	15	45	<5	0.88	3	12	80	2034	4.17	<10	0.27	315	27	0.01	1	1000	40	5	<20	26	<0.01	<10	5	<10	3	69
9	G34104	1.1	0.27	5	30	<5	0.53	3	7	65	706	3.23	<10	0.11	143	124	0.01	1	1120	36	<5	<20	28	<0.01	<10	3	<10	3	47
10	G34105	0.8	0.86	10	55	<5	1.27	2	7	54	714	3.52	<10	0.78	775	43	0.01	1	1080	14	<5	<20	33	<0.01	<10	8	<10	4	58
11	G34106	0.9	1.46	10	65	<5	1.63	2	7	57	1013	3.85	<10	1.38	1279	37	0.02	1	1040	20	<5	<20	44	<0.01	<10	23	<10	4	89
12	G34107	1.8	0.75	10	45	<5	2.21	3	10	73	1121	5.83	<10	0.86	1421	37	0.02	1	1420	36	<5	<20	61	<0.01	<10	10	<10	6	63
13	G34108	1.1	0.38	15	40	<5	1.15	2	6	74	823	3.99	<10	0.31	481	58	0.01	<1	920	30	<5	<20	36	<0.01	<10	5	<10	3	33
14	G34109	1.0	0.49	15	40	<5	0.94	2	10	66	1053	4.45	<10	0.46	440	43	0.01	<1	940	18	<5	<20	28	<0.01	<10	5	<10	3	48
15	G34110	1.9	0.47	25	40	<5	0.94	2	11	59	1681	4.74	<10	0.42	443	384	0.01	<1	980	48	<5	<20	28	<0.01	<10	4	<10	3	52
16	G34111	2.5	0.58	30	40	<5	0.91	3	9	74	2160	4.18	<10	0.51	475	117	0.01	<1	800	94	10	<20	33	<0.01	<10	6	<10	3	68
17	G34112	1.5	0.90	15	55	<5	1.10	2	7	61	1451	4.02	<10	0.75	616	56	0.01	<1	1110	18	<5	<20	30	<0.01	<10	10	<10	4	55
18	G34113	1.7	0.35	45	40	<5	0.69	3	8	82	996	5.83	<10	0.29	330	31	0.01	<1	960	26	10	<20	24	<0.01	<10	4	<10	3	35
19	G34114	2.4	0.24	65	50	5	0.68	6	8	67	501	9.68	<10	0.18	337	35	0.01	<1	850	156	15	<20	30	<0.01	<10	4	<10	2	106
20	G34115	1.3	0.77	15	50	<5	1.49	2	7	75	1033	3.74	<10	0.79	904	54	0.01	1	980	22	<5	<20	34	<0.01	<10	10	<10	4	63
21	G34116	1.5	0.52	10	40	<5	1.47	2	7	74	1394	4.49	<10	0.66	781	44	0.01	<1	990	28	<5	<20	41	<0.01	<10	8	<10	3	55
22	G34117	1.4	0.73	10	45	<5	1.85	2	9	67	1671	4.31	<10	0.90	837	35	0.01	<1	1020	20	<5	<20	45	<0.01	<10	9	<10	5	50
23	G34118	1.2	1.32	10	55	<5	1.59	2	8	83	1263	4.48	<10	1.30	920	38	0.02	1	970	16	<5	<20	40	<0.01	<10	23	<10	4	65
24	G34119	1.2	0.99	10	50	<5	1.92	2	10	59	1497	4.38	<10	1.11	904	35	0.01	<1	980	18	<5	<20	46	<0.01	<10	15	<10	5	54
25	G34120	1.1	0.92	10	50	<5	1.96	2	8	77	1105	4.23	<10	1.10	909	33	0.02	1	980	22	<5	<20	39	<0.01	<10	12	<10	5	57

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34121	1.5	1.20	10	55	<5	1.36	2	8	54	1369	4.52	<10	1.09	945	49	0.02	<1	900	32	<5	<20	36	<0.01	<10	23	<10	4	90
27	G34122	1.0	2.12	15	90	<5	1.56	2	8	43	1017	5.20	<10	1.67	1220	20	0.02	<1	1080	20	<5	<20	43	<0.01	<10	42	<10	5	133
28	G34123	2.0	1.19	20	60	<5	1.95	2	10	62	1506	4.71	<10	1.20	1395	48	0.02	1	1000	28	<5	<20	34	<0.01	<10	11	<10	5	92
29	G34124	3.3	1.45	20	65	<5	1.82	2	10	54	1745	4.89	<10	1.44	1395	43	0.01	1	990	18	<5	<20	34	<0.01	<10	16	<10	5	98
30	G34125	16.1	0.35	30	45	<5	1.75	4	9	67	2212	4.23	<10	0.52	1176	43	0.01	2	910	80	<5	<20	31	<0.01	<10	<1	<10	5	131
31	G34126	2.0	0.98	15	65	<5	3.31	2	7	50	925	3.51	<10	1.15	1207	31	0.01	2	1050	36	<5	<20	189	<0.01	<10	13	<10	6	145
32	G34127	1.2	0.48	10	45	<5	3.01	2	7	58	989	3.07	<10	0.81	1271	49	0.01	2	1000	78	<5	<20	106	<0.01	<10	1	<10	5	84
33	G34128	1.3	0.31	10	50	<5	1.98	3	8	65	1012	3.72	<10	0.58	1025	40	0.01	2	950	74	<5	<20	36	<0.01	<10	<1	<10	5	77
34	G34129	<0.2	0.97	10	315	<5	0.66	<1	7	97	3	2.45	<10	0.57	611	<1	0.07	7	900	6	<5	<20	90	0.13	<10	38	<10	4	57
35	G34130	3.4	1.03	70	80	<5	0.82	5	15	63	3244	3.92	20	0.56	270	210	0.03	18	470	122	40	<20	52	0.03	<10	42	<10	9	166
QC DATA:																													
Repeat:																													
1	G32996	<0.2	2.65	30	475	<5	4.78	2	27	32	6	6.29	<10	2.42	1145	1	0.03	1	990	16	<5	<20	188	0.08	<10	111	<10	10	81
10	G34105	0.8	0.81	10	50	<5	1.30	2	7	53	724	3.63	<10	0.78	785	44	0.01	<1	1060	16	<5	<20	36	<0.01	<10	8	<10	4	58
19	G34114	2.3	0.24	70	55	5	0.73	6	9	71	499	9.94	<10	0.20	368	34	0.01	<1	900	164	15	<20	32	<0.01	<10	2	<10	2	104
Resplit:																													
1	G32996	<0.2	2.73	35	510	<5	5.00	3	29	36	6	6.48	<10	2.54	1137	1	0.02	2	990	18	<5	<20	206	0.10	<10	118	<10	12	87
Standard:																													
Pb113		11.4	0.25	55	75	<5	1.71	48	3	2	2352	1.13	<10	0.11	1533	56	0.02	2	90	5514	5	<20	77	0.01	<10	7	<10	1	6919

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish



ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/n5431S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007-5432

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

2-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07012
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34131	0.67	0.020
2	G34132	0.48	0.014
3	G34133	0.61	0.018
4	G34134	0.69	0.020
5	G34135	0.51	0.015
6	G34136	0.89	0.026
7	G34137	0.58	0.017
8	G34138	0.52	0.015
9	G34139	0.49	0.014
10	G34140	0.72	0.021
11	G34141	0.62	0.018
12	G34142	0.73	0.021
13	G34143	0.91	0.027
14	G34144	0.82	0.024
15	G34145	0.91	0.027
16	G34146	1.86	0.054
17	G34147	1.02	0.030
18	G34148	1.27	0.037
19	G34149	0.95	0.028
20	G34150	0.81	0.024
21	G34151	0.88	0.026
22	G34152	<0.03	<0.001
23	G34153	0.73	0.021
24	G34154	0.73	0.021
25	G34155	0.52	0.015
26	G34156	1.00	0.029
27	G34157	0.74	0.022

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 2-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G34158	0.82	0.024
29	G34159	1.20	0.035
30	G34160	0.90	0.026
31	G34161	0.82	0.024
32	G34162	0.54	0.016
33	G34163	0.53	0.015
34	G34164	1.39	0.041
35	G34165	0.44	0.013

QC DATA:

Repeat:

1	G34131	0.68	0.020
6	G34136	0.95	0.028
7	G34137	0.57	0.017
10	G34140	0.72	0.021
15	G34145	0.89	0.026
18	G34148	1.34	0.039
19	G34149	0.95	0.028
26	G34156	1.05	0.031
29	G34159	1.14	0.033
34	G34164	1.41	0.041

Resplits:

1	G34131	0.58	0.017

Standard:

SJ32		2.66	0.078

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5432

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07012
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34131	1.1	0.72	10	40	<5	1.72	<1	8	64	1001	3.08	<10	0.94	965	39	0.02	2	1140	12	<5	<20	68	<0.01	<10	10	<10	5	48
2	G34132	0.8	0.70	10	50	<5	1.80	<1	7	57	968	2.67	<10	0.87	897	41	0.02	2	1170	12	<5	<20	62	<0.01	<10	9	<10	5	47
3	G34133	1.0	0.85	10	40	<5	1.79	<1	8	54	1207	3.78	<10	0.96	858	33	0.01	1	1110	14	<5	<20	34	<0.01	<10	11	<10	5	59
4	G34134	1.2	0.73	10	40	<5	1.93	<1	7	54	1424	3.44	<10	0.97	1121	45	0.02	<1	1080	18	<5	<20	37	<0.01	<10	10	<10	5	56
5	G34135	1.0	0.55	15	30	<5	1.66	2	8	65	991	3.96	<10	0.76	955	30	0.01	<1	1050	54	<5	<20	31	<0.01	<10	7	<10	4	126
6	G34136	1.4	0.81	15	50	<5	2.10	<1	7	51	1500	3.37	<10	1.07	1261	31	0.01	<1	1060	16	<5	<20	34	<0.01	<10	10	<10	5	92
7	G34137	1.0	0.47	15	35	<5	2.00	<1	7	63	1010	3.29	<10	0.71	1239	23	0.01	1	1160	30	<5	<20	35	<0.01	<10	6	<10	5	55
8	G34138	0.8	0.69	15	40	<5	2.03	<1	6	65	911	3.63	<10	0.98	1245	24	0.01	1	1100	14	<5	<20	35	<0.01	<10	8	<10	5	62
9	G34139	2.4	0.21	35	25	<5	1.41	2	9	70	1250	5.26	<10	0.47	722	20	0.01	<1	940	36	10	<20	30	<0.01	<10	6	<10	3	54
10	G34140	1.0	0.56	15	35	<5	1.90	<1	7	59	1319	2.92	<10	0.81	965	25	0.01	1	1090	18	<5	<20	68	<0.01	<10	6	<10	4	67
11	G34141	2.1	0.25	15	30	<5	1.34	1	6	90	1636	2.80	<10	0.47	785	35	0.01	2	940	40	<5	<20	39	<0.01	<10	4	<10	3	51
12	G34142	1.9	1.02	20	35	<5	1.05	1	9	54	1405	4.14	<10	1.05	861	27	0.02	<1	980	20	<5	<20	34	<0.01	<10	16	<10	3	122
13	G34143	1.5	1.35	20	40	<5	0.90	<1	9	55	1627	4.76	<10	1.07	711	20	0.02	<1	1040	24	<5	<20	39	<0.01	<10	22	<10	4	123
14	G34144	1.7	0.99	15	35	<5	1.93	1	9	61	1944	3.68	<10	0.78	951	26	0.02	1	1020	76	<5	<20	64	<0.01	<10	14	<10	5	107
15	G34145	2.4	0.73	20	45	<5	1.91	<1	7	53	1331	3.25	<10	0.75	1304	19	0.01	<1	1090	28	<5	<20	52	<0.01	<10	11	<10	5	96
16	G34146	3.3	1.04	35	50	<5	1.01	2	19	58	8633	4.22	20	0.58	208	546	0.04	64	220	60	20	<20	70	0.04	<10	37	<10	8	77
17	G34147	2.0	0.89	15	60	<5	1.83	<1	7	51	1353	3.12	<10	0.97	1463	18	0.01	1	1160	14	<5	<20	48	<0.01	<10	12	<10	5	132
18	G34148	1.7	1.03	15	50	<5	1.75	1	8	60	1837	3.64	<10	0.79	887	21	0.02	1	1020	38	<5	<20	80	<0.01	<10	16	<10	5	113
19	G34149	1.6	0.75	15	35	<5	2.67	1	7	54	1597	3.69	<10	0.85	1211	19	0.01	<1	1140	22	<5	<20	148	<0.01	<10	12	<10	6	100
20	G34150	1.9	0.63	40	35	<5	1.45	1	7	41	1250	3.56	<10	0.80	1269	19	<0.01	1	1170	24	5	<20	40	<0.01	<10	8	<10	6	158
21	G34151	11.6	0.17	105	25	<5	1.12	2	7	78	1460	4.06	<10	0.35	1052	6	0.01	<1	910	88	70	<20	33	<0.01	<10	5	<10	4	108
22	G34152	<0.2	1.01	10	285	<5	0.54	<1	7	91	4	2.27	<10	0.58	601	<1	0.08	6	980	8	<5	<20	90	0.13	<10	43	<10	4	53
23	G34153	8.5	0.24	30	35	<5	1.41	3	8	56	1882	4.45	<10	0.48	1362	6	0.01	<1	970	78	<5	<20	31	<0.01	<10	6	<10	4	206
24	G34154	4.0	0.53	20	40	<5	1.38	2	9	57	2228	4.67	<10	0.56	1267	8	0.01	<1	1010	58	<5	<20	38	<0.01	<10	8	<10	4	133
25	G34155	3.2	0.21	10	40	<5	1.33	4	8	81	3242	4.36	<10	0.30	1133	7	<0.01	<1	900	102	<5	<20	40	<0.01	<10	4	<10	3	138

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34156	2.6	0.50	25	35	<5	1.24	1	8	66	2179	4.68	<10	0.55	1319	6	<0.01	<1	1050	40	<5	<20	37	<0.01	<10	7	<10	4	68
27	G34157	4.1	0.58	35	35	<5	1.05	4	8	73	2821	4.67	<10	0.57	1034	10	<0.01	<1	990	146	15	<20	33	<0.01	<10	7	<10	4	243
28	G34158	4.3	0.53	15	35	<5	1.03	2	9	66	2282	4.43	<10	0.44	1083	5	<0.01	<1	960	48	<5	<20	30	<0.01	<10	6	<10	4	96
29	G34159	3.3	1.39	15	55	<5	0.59	1	8	68	2983	4.84	<10	0.84	615	8	<0.01	<1	1120	18	<5	<20	24	<0.01	<10	13	<10	4	121
30	G34160	3.7	0.86	20	35	<5	0.71	1	9	71	2650	5.10	<10	0.53	698	7	<0.01	<1	910	28	<5	<20	27	<0.01	<10	10	<10	3	79
31	G34161	1.4	0.63	25	30	<5	0.40	2	8	79	1400	6.09	<10	0.33	347	9	<0.01	<1	950	40	<5	<20	18	<0.01	<10	9	<10	2	100
32	G34162	2.0	0.32	10	35	<5	0.52	1	7	78	1634	3.85	<10	0.12	320	8	<0.01	<1	980	52	<5	<20	22	<0.01	<10	6	<10	3	46
33	G34163	1.8	0.46	15	35	<5	1.42	4	7	63	1393	3.48	<10	0.43	1172	12	<0.01	1	1110	40	<5	<20	50	<0.01	<10	9	<10	5	125
34	G34164	1.8	1.05	20	35	<5	1.92	1	7	81	1493	4.37	<10	0.76	1145	14	0.02	1	950	32	<5	<20	95	<0.01	<10	13	<10	6	150
35	G34165	2.1	0.35	15	35	<5	0.27	<1	7	82	1752	2.61	<10	0.19	145	16	<0.01	2	1110	62	<5	<20	18	<0.01	<10	7	<10	3	57
QC DATA:																													
Repeat:																													
1	G34131	1.2	0.71	10	35	<5	1.82	<1	8	66	1001	3.11	<10	0.92	994	32	0.02	2	1140	14	<5	<20	73	<0.01	<10	10	<10	5	49
10	G34140	0.9	0.55	10	35	<5	1.57	<1	6	59	1303	2.92	<10	0.81	948	25	0.01	1	1090	16	<5	<20	69	<0.01	<10	7	<10	4	66
19	G34149	1.4	0.76	15	40	<5	2.63	1	7	56	1570	3.77	<10	0.83	1236	21	0.01	<1	1140	22	<5	<20	157	<0.01	<10	13	<10	6	104
Resplit:																													
1	G34131	0.7	0.71	10	45	<5	1.77	<1	7	66	900	2.91	<10	0.92	1026	33	0.01	2	1130	14	<5	<20	80	<0.01	<10	11	<10	5	57
Standard:																													
Pb113		12.2	0.26	40	70	<5	1.64	46	2	2	2349	1.13	<10	0.11	1597	62	0.01	1	80	5538	5	<20	80	0.01	<10	7	<10	1	7041

Aqua Regia Digestion
ICP Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl/jl
df/n5432S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007-5433

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

2-Aug-07

No. of samples received: 45
Sample Type: Core
Project: KSM
Shipment #: 07011
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36071	0.78	0.023
2	G36072	1.00	0.029
3	G36073	0.69	0.020
4	G36074	0.81	0.024
5	G36075	0.67	0.020
6	G36076	0.74	0.022
7	G36077	0.99	0.029
8	G36078	1.03	0.030
9	G36079	0.67	0.020
10	G36080	0.88	0.026
11	G36081	0.82	0.024
12	G36082	1.13	0.033
13	G36083	1.15	0.034
14	G36084	0.86	0.025
15	G36085	0.82	0.024
16	G36086	0.87	0.025
17	G36087	1.01	0.029
18	G36088	0.89	0.026
19	G36089	1.84	0.054
20	G36090	0.71	0.021
21	G36091	0.44	0.013
22	G36092	0.76	0.022
23	G36093	1.03	0.030
24	G36094	0.72	0.021
25	G36095	0.64	0.019
26	G36096	0.54	0.016
27	G36097	0.99	0.029

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 2-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G36098	0.96	0.028
29	G36099	0.45	0.013
30	G36100	0.63	0.018
31	G36101	0.92	0.027
32	G36102	0.96	0.028
33	G36103	1.13	0.033
34	G36104	0.96	0.028
35	G36105	1.55	0.045
36	G36106	0.72	0.021
37	G36107	0.84	0.024
38	G36108	1.20	0.035
39	G36109	0.94	0.027
40	G36110	0.98	0.029
41	G36111	0.69	0.020
42	G36112	1.06	0.031
43	G36113	0.88	0.026
44	G36114	0.99	0.029
45	G36115	0.93	0.027

QC DATA:

Repeat:

1	G36071	0.81	0.024
2	G36072	1.03	0.030
8	G36078	1.13	0.033
10	G36080	0.82	0.024
13	G36083	1.14	0.033
23	G36093	1.14	0.033
27	G36097	0.89	0.026
33	G36103	1.12	0.033
35	G36105	1.60	0.047
36	G36106	0.78	0.023
38	G36108	1.19	0.035
40	G36110	1.05	0.031
42	G36112	0.98	0.029

Resplits:

1	G36071	0.81	0.024
36	G36106	0.79	0.023

Standard:

SJ32		2.64	0.077
SJ32		2.63	0.077
S125		1.81	0.053

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5433

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 45
Sample Type: Core
Project: KSM
Shipment #: 07011
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36071	22.8	0.57	35	30	<5	0.23	3	9	114	2090	5.07	<10	0.32	153	26	0.02	3	1160	90	10	<20	29	<0.01	<10	11	<10	3	142
2	G36072	4.8	0.81	15	40	<5	0.31	<1	11	92	2901	4.60	<10	0.60	251	20	0.01	3	1290	18	<5	<20	40	<0.01	<10	19	<10	4	59
3	G36073	2.7	0.64	25	45	<5	0.27	<1	9	91	2264	3.74	<10	0.39	148	32	0.01	3	1360	18	<5	<20	32	<0.01	<10	15	<10	4	34
4	G36074	3.1	0.55	15	45	<5	0.24	<1	11	106	2419	4.46	<10	0.35	167	34	0.01	3	1200	20	<5	<20	27	<0.01	<10	15	<10	3	33
5	G36075	5.9	0.65	25	40	<5	0.27	<1	10	98	2102	4.66	<10	0.48	275	39	0.01	3	1330	20	<5	<20	37	<0.01	<10	17	<10	4	53
6	G36076	7.3	0.53	35	35	<5	0.30	1	13	147	3745	4.64	<10	0.38	278	45	0.01	4	1230	20	<5	<20	36	<0.01	<10	16	<10	4	46
7	G36077	3.2	1.23	30	55	<5	0.60	<1	10	84	1973	4.43	<10	1.06	767	46	0.02	4	1460	18	<5	<20	80	<0.01	<10	24	<10	5	62
8	G36078	5.8	0.64	20	40	<5	0.54	1	10	103	3237	4.21	<10	0.51	409	61	0.01	3	1390	26	<5	<20	71	<0.01	<10	16	<10	5	40
9	G36079	1.7	0.91	20	50	<5	0.80	<1	9	108	2239	3.78	<10	0.78	497	74	0.02	4	1190	20	<5	<20	135	<0.01	<10	23	<10	5	52
10	G36080	1.8	1.23	15	75	<5	1.02	1	11	117	2636	4.75	<10	0.99	499	50	0.02	4	1190	16	<5	<20	197	<0.01	<10	39	<10	5	52
11	G36081	1.5	0.95	20	45	<5	0.79	<1	10	98	1571	4.64	<10	0.73	451	41	0.02	3	1350	20	<5	<20	127	<0.01	<10	22	<10	5	37
12	G36082	2.5	0.98	20	55	<5	0.84	<1	10	94	3044	4.29	<10	0.80	587	70	0.01	4	1220	16	<5	<20	129	<0.01	<10	22	<10	5	40
13	G36083	2.1	1.01	20	55	<5	0.94	<1	10	89	2681	4.45	<10	0.84	615	40	0.01	3	1280	16	<5	<20	145	<0.01	<10	22	<10	6	42
14	G36084	1.6	0.90	20	50	<5	0.93	<1	11	83	2491	4.02	<10	0.79	582	63	0.01	3	1390	18	<5	<20	165	<0.01	<10	19	<10	6	37
15	G36085	1.6	1.12	20	60	<5	1.26	<1	8	119	2681	4.15	<10	0.93	648	44	0.01	4	1220	16	<5	<20	169	<0.01	<10	26	<10	5	45
16	G36086	1.8	0.92	15	140	<5	3.58	<1	10	110	2527	4.23	<10	0.75	653	35	0.02	4	1180	20	<5	<20	3138	<0.01	<10	31	<10	5	42
17	G36087	2.9	0.80	20	40	<5	0.75	<1	13	131	3100	4.08	<10	0.63	546	53	0.01	4	1040	18	<5	<20	139	<0.01	<10	19	<10	4	42
18	G36088	2.7	1.26	25	50	<5	0.42	<1	11	99	2523	5.12	<10	0.91	619	40	0.01	4	1520	18	<5	<20	53	<0.01	<10	28	<10	5	69
19	G36089	3.9	1.12	40	60	<5	1.23	2	21	58	8710	4.60	20	0.57	223	643	0.04	75	260	66	20	<20	79	0.05	<10	41	<10	9	88
20	G36090	7.9	0.35	65	40	<5	0.33	1	14	155	2129	5.46	<10	0.11	149	60	0.01	4	1360	30	10	<20	38	<0.01	<10	11	<10	4	60
21	G36091	9.5	0.25	250	40	<5	0.31	2	11	121	2295	6.01	<10	0.02	40	32	0.01	2	1360	32	35	<20	28	<0.01	<10	10	<10	4	101
22	G36092	14.4	0.22	330	40	<5	0.28	2	10	162	3150	3.99	<10	0.01	37	28	0.01	4	1220	32	45	<20	28	<0.01	<10	8	<10	4	133
23	G36093	7.0	0.22	105	35	<5	0.29	1	11	130	3224	4.90	<10	0.02	33	45	0.01	3	1390	26	15	<20	28	<0.01	<10	7	<10	4	99
24	G36094	11.3	0.24	215	35	<5	0.31	1	11	131	2799	4.82	<10	0.02	38	47	0.01	3	1480	34	35	<20	32	<0.01	<10	9	<10	5	87
25	G36095	21.9	0.24	845	40	<5	0.27	3	9	110	2246	4.91	<10	0.02	44	38	0.01	3	1390	46	110	<20	28	<0.01	<10	10	<10	4	227

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007- 5433 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36096	3.6	0.27	70	35	<5	0.28	<1	9	110	1633	4.61	<10	0.06	74	55	0.01	3	1440	24	10	<20	29	<0.01	<10	10	<10	4	44
27	G36097	4.4	0.25	75	35	<5	0.25	1	15	119	2978	5.88	<10	0.05	58	37	0.01	2	1310	32	10	<20	27	<0.01	<10	7	<10	3	58
28	G36098	4.7	0.24	75	30	<5	0.30	1	12	106	3082	5.52	<10	0.03	36	25	0.02	3	1530	40	10	<20	30	<0.01	<10	8	<10	4	37
29	G36099	2.7	0.27	25	40	<5	0.24	2	9	136	1932	3.54	<10	0.07	102	101	0.01	4	1190	58	<5	<20	27	<0.01	<10	9	<10	3	126
30	G36100	2.0	0.62	25	45	<5	0.32	<1	10	109	1656	4.54	<10	0.42	374	57	0.01	3	1390	22	<5	<20	40	<0.01	<10	17	<10	4	68
31	G36101	1.9	0.70	25	40	<5	0.34	<1	10	109	2159	4.45	<10	0.52	457	43	0.01	3	1330	22	<5	<20	61	<0.01	<10	20	<10	4	80
32	G36102	3.0	0.46	25	40	<5	0.21	1	12	121	3687	4.06	<10	0.30	249	84	0.01	3	980	30	<5	<20	26	<0.01	<10	13	<10	3	80
33	G36103	3.5	0.48	30	45	<5	0.27	2	11	112	4878	4.62	<10	0.27	210	25	0.01	4	1340	26	<5	<20	28	<0.01	<10	15	<10	4	98
34	G36104	4.7	0.51	25	40	<5	0.28	1	12	105	4164	4.28	<10	0.31	214	27	0.01	3	1530	26	<5	<20	29	<0.01	<10	18	<10	5	66
35	G36105	29.6	0.30	40	35	<5	0.27	3	12	112	3727	4.30	<10	0.11	92	61	0.01	4	1390	106	10	<20	29	<0.01	<10	10	<10	4	154
36	G36106	8.6	0.54	30	60	<5	0.28	1	11	104	2406	4.37	<10	0.29	192	57	0.02	4	1510	26	<5	<20	29	<0.01	<10	16	<10	4	70
37	G36107	4.2	0.93	45	60	<5	0.26	<1	11	105	1961	4.45	<10	0.67	489	64	0.02	4	1380	16	<5	<20	26	<0.01	<10	22	<10	4	60
38	G36108	4.8	0.78	55	45	<5	0.26	1	15	97	3267	5.76	<10	0.56	420	38	0.02	3	1170	32	<5	<20	37	<0.01	<10	22	<10	3	64
39	G36109	5.2	0.86	45	50	<5	0.57	<1	10	69	3195	4.16	<10	0.67	536	55	0.02	3	1430	18	<5	<20	145	<0.01	<10	21	<10	5	47
40	G36110	3.2	0.86	50	45	<5	0.43	<1	12	107	1992	5.07	<10	0.65	459	58	0.02	3	1440	18	<5	<20	77	<0.01	<10	24	<10	4	52
41	G36111	3.2	0.57	20	45	<5	0.27	<1	10	105	2838	3.98	<10	0.36	186	73	0.02	4	1330	22	<5	<20	39	<0.01	<10	19	<10	4	32
42	G36112	4.2	0.49	10	40	<5	0.31	<1	11	113	3655	4.34	<10	0.32	202	27	0.01	3	1160	26	<5	<20	66	<0.01	<10	23	<10	4	32
43	G36113	3.6	0.57	50	40	<5	0.31	2	10	108	1598	4.08	<10	0.37	219	52	0.02	4	1460	28	<5	<20	44	<0.01	<10	18	<10	4	100
44	G36114	5.4	0.49	30	40	<5	0.35	1	12	94	3790	3.98	<10	0.26	204	32	0.02	3	1400	36	<5	<20	57	<0.01	<10	15	<10	5	55
45	G36115	2.8	0.71	20	40	<5	0.40	<1	11	94	2566	4.96	<10	0.50	345	64	0.02	4	1570	20	<5	<20	62	<0.01	<10	21	<10	5	48
QC DATA:																													
Repeat:																													
1	G36071	22.8	0.55	35	35	<5	0.24	3	9	116	2091	5.21	<10	0.33	153	24	0.01	3	1170	84	10	<20	29	<0.01	10	11	<10	3	132
10	G36080	2.0	1.21	15	80	<5	1.16	<1	12	119	2654	4.86	<10	1.00	542	57	0.02	4	1250	18	<5	<20	202	<0.01	<10	38	<10	6	55
36	G36106	8.6	0.50	35	40	<5	0.32	1	11	108	2478	4.52	<10	0.30	193	62	0.02	4	1580	24	<5	<20	30	<0.01	<10	14	<10	4	63
Resplit:																													
1	G36071	23.4	0.62	40	35	<5	0.23	3	10	120	2126	5.71	<10	0.37	173	26	0.01	3	1240	84	10	<20	31	<0.01	10	14	<10	3	144
36	G36106	8.9	0.52	35	45	<5	0.34	1	11	114	2465	4.29	<10	0.31	211	66	0.02	4	1480	24	<5	<20	31	<0.01	10	15	<10	4	62
45	G36115	2.8	0.63	20	35	<5	0.46	<1	13	96	2538	4.67	<10	0.42	330	150	0.02	3	1560	20	<5	<20	65	<0.01	10	18	<10	5	47
Standard:																													
Pb113		10.6	0.25	55	65	<5	1.60	45	2	2	2302	1.08	<10	0.10	1561	59	0.01	<1	70	5584	<5	<20	80	<0.01	<10	9	<10	1	7072
Pb113		10.4	0.26	55	70	<5	1.93	46	2	1	2332	1.10	<10	0.10	1605	60	0.01	<1	80	5676	<5	<20	84	0.01	<10	7	<10	1	7088

Aqua Regia Digestion
ICP Finish

JJ/nl/
df/n5432S
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007-5437

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

2-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07013
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36116	0.87	0.025
2	G36117	0.94	0.027
3	G36118	1.07	0.031
4	G36119	<0.03	<0.001
5	G36120	1.01	0.029
6	G36121	0.74	0.022
7	G36122	0.83	0.024
8	G36123	1.09	0.032
9	G36124	1.17	0.034
10	G36125	0.66	0.019
11	G36126	<0.03	<0.001
12	G36127	0.03	0.001
13	G36128	0.09	0.003
14	G36129	<0.03	<0.001
15	G36130	<0.03	<0.001
16	G36131	<0.03	<0.001
17	G36132	0.24	0.007
18	G36133	0.21	0.006
19	G36134	0.28	0.008
20	G36135	0.07	0.002
21	G36136	0.04	0.001
22	G36137	0.05	0.001
23	G36138	0.05	0.001
24	G36139	0.06	0.002
25	G36140	0.06	0.002
26	G36141	0.03	0.001
27	G36142	0.05	0.001

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 2-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G36143	0.13	0.004
29	G36144	0.28	0.008
30	G36145	0.10	0.003
31	G36146	1.80	0.052
32	G36147	0.16	0.005
33	G36148	0.05	0.001
34	G36149	0.08	0.002
35	G36150	0.07	0.002
QC DATA:			
Repeat:			
1	G36116	0.87	0.025
3	G36118	1.05	0.031
8	G36123	1.04	0.030
9	G36124	1.12	0.033
10	G36125	0.65	0.019
19	G36134	0.30	0.009
Resplit:			
1	G36116	0.95	0.028
Standard:			
SJ32		2.68	0.078

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3· '-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5437

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07013
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36116	2.0	0.57	20	40	<5	0.36	2	10	83	1858	4.23	<10	0.40	295	53	0.03	2	1440	16	<5	<20	54	<0.01	<10	14	<10	4	37
2	G36117	2.9	0.48	25	45	<5	0.26	2	13	111	3110	3.85	<10	0.28	178	98	0.03	3	1290	14	<5	<20	30	<0.01	<10	11	<10	4	43
3	G36118	2.7	0.83	20	45	<5	0.30	3	13	83	2199	4.44	<10	0.67	366	72	0.03	3	1390	16	<5	<20	39	<0.01	<10	19	<10	5	62
4	G36119	<0.2	0.98	<5	265	<5	0.55	1	6	102	4	2.19	<10	0.56	534	2	0.11	6	930	8	<5	<20	87	0.13	<10	40	<10	4	49
5	G36120	3.2	0.84	15	45	<5	0.28	2	12	121	2462	3.87	<10	0.70	376	69	0.03	3	1260	14	<5	<20	40	<0.01	<10	24	<10	5	68
6	G36121	2.2	0.90	15	45	<5	0.30	2	10	87	2038	4.02	<10	0.79	368	67	0.03	3	1390	16	<5	<20	42	<0.01	<10	21	<10	5	70
7	G36122	2.8	0.71	10	40	<5	0.30	6	12	111	2537	4.39	<10	0.58	304	58	0.03	3	1240	40	<5	<20	48	<0.01	<10	19	<10	4	148
8	G36123	2.8	0.74	15	40	<5	0.27	3	12	133	2882	4.64	<10	0.60	291	85	0.03	3	1180	16	<5	<20	43	<0.01	<10	20	<10	5	54
9	G36124	3.5	0.59	20	40	<5	0.30	3	12	102	3393	4.37	<10	0.46	223	62	0.03	3	1300	18	<5	<20	47	<0.01	<10	17	<10	5	41
10	G36125	2.0	0.69	25	45	<5	0.40	2	10	93	1443	4.07	<10	0.46	328	103	0.03	3	1500	16	<5	<20	47	0.01	<10	28	<10	5	42
11	G36126	0.5	0.62	10	230	<5	0.14	1	4	80	274	1.73	<10	0.44	374	4	0.02	5	830	6	<5	<20	10	<0.01	<10	113	<10	3	38
12	G36127	0.4	0.40	20	90	<5	0.31	2	8	95	407	2.79	<10	0.18	273	2	0.02	8	770	8	<5	<20	25	<0.01	<10	147	<10	3	27
13	G36128	1.1	0.60	25	55	<5	2.44	2	11	77	1098	2.39	<10	0.34	845	3	0.02	9	1290	22	<5	<20	143	<0.01	<10	152	<10	5	34
14	G36129	<0.2	1.44	25	105	<5	1.05	2	12	21	184	3.29	10	0.83	1002	2	0.02	9	1320	12	<5	<20	55	<0.01	<10	26	<10	9	96
15	G36130	<0.2	1.42	20	70	<5	2.94	2	11	22	49	3.31	10	0.88	1157	<1	0.02	6	1210	10	<5	<20	147	0.01	<10	27	<10	8	81
16	G36131	<0.2	1.45	20	80	<5	2.48	2	12	27	38	3.62	10	0.95	1117	<1	0.02	6	1240	10	<5	<20	108	<0.01	<10	28	<10	8	78
17	G36132	0.9	0.79	40	90	<5	2.07	2	12	58	718	2.86	<10	0.56	802	2	0.03	10	1800	28	<5	<20	113	0.01	<10	146	<10	5	46
18	G36133	0.7	0.91	20	115	<5	0.54	2	10	76	426	2.58	<10	0.74	486	2	0.05	10	1750	14	<5	<20	32	0.03	<10	141	<10	5	41
19	G36134	1.3	0.87	60	85	<5	1.24	2	10	71	776	2.85	<10	0.66	882	2	0.03	9	1940	26	<5	<20	72	0.02	<10	113	<10	6	51
20	G36135	0.8	0.58	10	110	<5	1.09	1	7	102	612	1.88	<10	0.49	506	6	0.04	11	1260	14	<5	<20	77	0.02	<10	103	<10	4	27
21	G36136	0.6	0.51	5	90	<5	0.84	<1	4	96	618	1.14	<10	0.37	337	6	0.04	5	690	12	<5	<20	75	<0.01	<10	64	<10	3	20
22	G36137	0.6	0.39	5	70	<5	0.82	<1	4	88	790	1.18	<10	0.22	318	4	0.04	5	310	8	<5	<20	73	<0.01	<10	117	<10	2	19
23	G36138	0.7	0.50	5	70	<5	1.16	<1	5	74	674	1.39	<10	0.36	414	5	0.03	6	1020	10	<5	<20	107	0.01	<10	92	<10	4	27
24	G36139	0.8	0.51	5	65	<5	1.34	1	5	99	738	1.66	<10	0.39	424	6	0.03	5	1090	14	<5	<20	125	<0.01	<10	115	<10	4	24
25	G36140	0.7	0.53	5	80	<5	1.17	<1	5	99	692	1.60	<10	0.41	405	4	0.04	5	990	12	<5	<20	109	<0.01	<10	119	<10	4	24

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36141	0.4	0.78	10	110	<5	1.95	1	6	69	686	1.77	10	0.68	544	3	0.05	8	2760	8	<5	<20	143	0.03	<10	164	<10	8	37
27	G36142	0.4	0.54	5	105	<5	1.12	<1	5	75	847	1.26	<10	0.48	381	5	0.04	6	1560	8	<5	<20	91	0.02	<10	76	<10	5	24
28	G36143	1.3	0.85	20	100	<5	1.83	2	11	76	1243	2.35	<10	0.91	712	14	0.03	11	1540	20	<5	<20	134	0.05	<10	138	<10	7	32
29	G36144	3.1	1.13	35	65	<5	0.97	5	19	64	2644	3.71	20	0.62	189	197	0.05	13	530	50	5	<20	67	0.04	<10	41	<10	9	274
30	G36145	1.2	1.05	10	135	<5	2.77	1	10	66	1351	2.26	<10	1.15	846	6	0.05	11	1870	12	<5	<20	201	0.06	<10	179	<10	8	42
31	G36146	3.8	1.07	35	55	<5	0.99	4	20	65	8518	4.13	20	0.59	201	598	0.05	69	240	58	20	<20	67	0.04	<10	38	<10	9	84
32	G36147	1.4	0.85	10	105	<5	1.79	1	9	83	1663	1.96	<10	0.80	563	18	0.05	11	1910	12	<5	<20	127	0.05	<10	161	<10	8	33
33	G36148	0.5	1.13	10	140	<5	2.00	2	10	80	864	2.88	<10	1.16	650	1	0.08	11	1990	14	<5	<20	120	0.08	<10	265	<10	7	55
34	G36149	0.4	0.98	10	205	<5	2.03	2	13	64	1039	3.17	<10	0.91	680	<1	0.06	7	1920	24	<5	<20	127	0.05	<10	447	<10	7	66
35	G36150	0.5	0.84	10	190	<5	1.47	2	12	59	1292	2.47	<10	0.71	542	<1	0.04	8	2250	20	<5	<20	86	0.04	<10	232	<10	7	52
QC DATA:																													
Repeat:																													
1	G36116	2.0	0.56	20	40	<5	0.36	3	11	82	1894	4.29	<10	0.39	296	53	0.03	2	1460	16	<5	<20	54	<0.01	<10	14	<10	4	38
10	G36125	2.0	0.65	25	40	<5	0.40	3	9	92	1397	4.08	<10	0.44	318	115	0.03	3	1500	16	<5	<20	47	0.01	<10	27	<10	5	44
19	G36134	1.3	0.85	60	75	<5	1.20	2	11	71	794	2.90	<10	0.69	874	2	0.03	9	1990	24	<5	<20	73	0.02	<10	113	<10	6	51
Resplit:																													
1	G36116	2.2	0.57	25	40	<5	0.37	3	12	106	1968	4.41	<10	0.42	299	47	0.03	3	1510	16	<5	<20	61	<0.01	<10	15	<10	5	41
Standard:																													
Pb113		11.0	0.26	55	70	<5	1.64	44	2	7	2350	1.12	<10	0.11	1584	57	0.02	<1	210	5536	10	<20	86	<0.01	<10	6	<10	<1	7049

ICP: Aqua Regia Digestion/ICP-AES Finish
Ag: Aqua Regia Digestion/AA Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5437
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007-5438

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

2-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07014
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36151	0.05	0.001
2	G36152	0.12	0.003
3	G36153	0.05	0.001
4	G36154	<0.03	<0.001
5	G36155	<0.03	<0.001
6	G36156	0.06	0.002
7	G36157	0.04	0.001
8	G36158	<0.03	<0.001
9	G36159	0.07	0.002
10	G36160	0.09	0.003
11	G36161	0.15	0.004
12	G36162	0.04	0.001
13	G36163	0.10	0.003
14	G36164	0.15	0.004
15	G36165	0.10	0.003
16	G36166	<0.03	<0.001
17	G36167	<0.03	<0.001
18	G36168	<0.03	<0.001
19	G36169	<0.03	<0.001
20	G36170	<0.03	<0.001
21	G36171	<0.03	<0.001
22	G36172	0.06	0.002
23	G36173	0.23	0.007
24	G36174	0.05	0.001
25	G36175	0.08	0.002
26	G36176	0.19	0.006
27	G36177	<0.03	<0.001

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 2-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G36178	0.10	0.003
29	G36179	0.07	0.002
30	G36180	0.04	0.001
31	G36181	0.05	0.001
32	G36182	0.08	0.002
33	G36183	0.96	0.028
34	G36184	0.04	0.001
35	G36185	0.07	0.002

QC DATA:

Repeat:			
1	G36151	0.05	0.001
10	G36160	0.08	0.002
19	G36169	<0.03	<0.001
Resplits:			
1	G36151	0.04	0.001
Standard:			
SJ32		2.63	0.077

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3- 07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5438

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07014
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36151	0.6	1.10	15	145	<5	2.40	2	13	66	739	2.84	<10	0.91	901	<1	0.04	10	2110	32	<5	<20	138	0.05	<10	575	<10	7	84
2	G36152	0.5	1.14	25	115	<5	3.24	1	8	66	273	2.12	<10	1.04	1046	<1	0.05	11	2010	14	<5	<20	182	0.04	<10	421	<10	7	49
3	G36153	0.4	0.86	10	140	<5	2.70	1	11	63	600	1.77	<10	0.76	738	7	0.08	10	2080	10	<5	<20	128	0.04	<10	134	<10	8	32
4	G36154	0.2	0.83	5	135	<5	3.54	1	6	79	362	1.67	<10	0.78	1078	1	0.09	9	1490	6	<5	<20	205	0.03	<10	162	<10	8	33
5	G36155	0.2	0.67	10	155	<5	3.49	1	7	63	629	1.45	<10	0.61	1116	7	0.06	8	2030	10	<5	<20	216	0.03	<10	106	<10	10	26
6	G36156	0.4	1.06	10	235	<5	2.82	2	14	66	935	2.83	<10	1.01	902	1	0.08	12	2080	16	<5	<20	175	0.04	<10	281	<10	7	54
7	G36157	0.4	1.06	15	290	<5	2.48	3	14	95	930	3.19	<10	1.07	957	2	0.08	20	1700	20	<5	<20	183	0.06	<10	331	<10	6	82
8	G36158	0.3	0.96	10	285	<5	2.84	2	12	125	899	3.01	<10	0.95	1014	4	0.08	26	1700	14	<5	<20	224	0.04	<10	346	<10	7	60
9	G36159	0.5	0.41	10	145	<5	2.75	3	14	71	1011	3.28	<10	0.79	1012	3	0.04	15	1540	18	<5	<20	156	0.01	<10	146	<10	8	38
10	G36160	0.6	0.55	10	275	<5	2.62	2	9	71	1030	2.63	<10	0.71	882	2	0.04	7	1480	12	<5	<20	188	<0.01	<10	125	<10	7	47
11	G36161	1.0	1.10	25	315	<5	4.41	3	13	45	2035	3.20	10	0.78	1441	10	0.03	22	1950	26	<5	<20	260	<0.01	<10	99	<10	12	63
12	G36162	<0.2	0.78	5	160	<5	1.48	1	5	61	432	1.50	<10	0.41	439	2	0.03	12	920	10	<5	<20	91	<0.01	<10	65	<10	3	37
13	G36163	0.5	0.99	10	290	<5	3.46	2	11	58	1080	2.92	<10	0.66	1069	2	0.04	11	910	24	<5	<20	233	<0.01	<10	141	<10	5	60
14	G36164	0.7	0.60	5	175	<5	2.28	1	12	44	1427	1.98	<10	0.30	641	3	0.05	5	1190	30	<5	<20	143	<0.01	<10	71	<10	4	38
15	G36165	0.8	1.30	15	170	<5	4.63	2	14	38	1398	3.29	<10	1.00	1567	<1	0.03	12	1270	24	<5	<20	197	<0.01	<10	85	<10	7	72
16	G36166	0.2	1.35	20	205	<5	4.25	2	11	24	340	2.76	<10	0.90	1316	1	0.02	6	990	12	<5	<20	201	0.01	<10	37	<10	7	54
17	G36167	<0.2	1.46	15	235	<5	3.51	2	11	25	33	2.97	10	0.97	1011	2	0.02	5	960	8	<5	<20	155	<0.01	<10	27	<10	7	62
18	G36168	<0.2	1.53	15	385	<5	3.78	2	11	30	24	3.20	10	1.06	1061	<1	0.03	5	940	10	<5	<20	159	<0.01	<10	29	<10	7	63
19	G36169	<0.2	1.32	20	195	<5	4.33	2	11	23	33	2.80	10	0.81	1227	1	0.02	5	950	10	<5	<20	174	<0.01	<10	21	<10	8	61
20	G36170	<0.2	1.02	15	140	<5	3.90	2	10	14	35	2.36	10	0.47	995	<1	0.01	5	1010	12	<5	<20	152	<0.01	<10	17	<10	7	51
21	G36171	<0.2	1.02	20	340	<5	4.15	2	12	18	40	2.43	20	0.35	1001	2	0.02	6	1060	12	<5	<20	152	<0.01	<10	16	<10	8	50
22	G36172	0.9	0.91	75	135	<5	3.89	2	14	57	768	2.16	<10	0.51	1052	29	0.03	14	930	34	<5	<20	144	<0.01	<10	97	<10	5	41
23	G36173	2.3	1.23	50	95	<5	7.49	3	14	46	1484	3.19	<10	0.86	2180	31	0.02	15	1030	40	5	<20	243	0.01	<10	72	<10	7	49
24	G36174	2.1	1.18	15	130	10	7.38	4	12	48	961	4.32	<10	0.86	2752	12	0.03	10	730	270	<5	<20	313	0.03	<10	386	<10	9	90
25	G36175	2.2	1.09	15	125	15	6.34	3	11	44	1347	3.95	<10	0.68	2268	10	0.03	9	730	116	<5	<20	277	0.02	<10	299	<10	8	83

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36176	2.7	1.09	15	105	20	3.83	4	15	58	2019	4.16	10	0.81	1487	6	0.04	11	1130	206	<5	<20	202	0.03	<10	306	<10	6	163
27	G36177	<0.2	1.10	<5	285	<5	0.68	2	7	87	4	2.24	<10	0.58	524	2	0.12	6	910	10	<5	<20	90	0.14	<10	43	<10	5	58
28	G36178	2.7	1.41	15	145	15	4.02	4	15	63	1427	4.56	10	1.11	1633	25	0.04	15	1030	296	<5	<20	200	0.06	<10	392	<10	7	139
29	G36179	4.0	1.57	15	145	30	4.76	5	17	62	1252	5.49	10	1.22	1796	23	0.03	20	930	300	<5	<20	253	0.06	<10	420	<10	7	171
30	G36180	2.2	1.06	10	130	5	4.79	4	13	59	1204	3.58	<10	0.69	1430	11	0.04	13	1050	232	<5	<20	223	0.04	<10	265	<10	6	184
31	G36181	1.9	1.33	15	155	10	5.53	4	13	78	1040	4.33	10	0.90	1876	34	0.03	17	700	332	<5	<20	232	0.06	<10	387	<10	7	195
32	G36182	2.0	1.22	15	125	10	6.24	5	16	66	1145	5.12	<10	0.96	1948	12	0.03	12	790	352	<5	<20	257	0.06	<10	409	<10	7	279
33	G36183	3.6	1.22	65	90	<5	0.81	6	16	70	3403	3.94	20	0.48	253	205	0.04	18	360	118	25	<20	47	0.03	<10	38	<10	9	167
34	G36184	2.4	1.00	10	120	5	4.95	4	13	52	1087	3.58	<10	0.59	1313	5	0.04	5	1080	518	<5	<20	218	0.03	<10	223	<10	4	176
35	G36185	2.1	0.79	10	105	10	4.44	3	12	56	872	3.01	<10	0.45	1326	9	0.04	6	1090	300	<5	<20	184	0.02	<10	155	<10	5	122
QC DATA:																													
Repeat:																													
1	G36151	0.5	1.04	15	135	<5	2.29	2	12	64	715	2.77	<10	0.89	861	<1	0.03	10	2080	24	<5	<20	135	0.05	<10	533	<10	7	71
10	G36160	0.6	0.53	5	255	<5	2.65	2	9	67	1005	2.62	<10	0.68	883	2	0.04	7	1470	10	<5	<20	183	<0.01	<10	117	<10	7	47
19	G36169	<0.2	1.45	20	200	<5	4.43	2	11	24	34	2.90	10	0.84	1254	1	0.02	5	1000	12	<5	<20	177	<0.01	<10	21	<10	8	65
Resplit:																													
1	G36151	0.4	1.13	15	140	<5	2.36	3	13	77	714	2.97	<10	0.84	803	<1	0.03	10	2120	22	<5	<20	135	0.05	<10	560	<10	7	77
Standard:																													
Pb113		11.4	0.30	60	70	<5	1.66	47	2	7	2322	1.21	<10	0.11	1562	55	0.02	<1	80	5538	5	<20	80	0.01	<10	7	<10	<1	7026

Aqua Regia Digestion
ICP Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/n5437
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007-5439

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

2-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07015
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36186	0.47	0.014
2	G36187	0.20	0.006
3	G36188	0.08	0.002
4	G36189	0.14	0.004
5	G36190	0.20	0.006
6	G36191	0.14	0.004
7	G36192	0.12	0.003
8	G36193	0.12	0.003
9	G36194	0.36	0.010
10	G36195	0.25	0.007
11	G36196	0.11	0.003
12	G36197	<0.03	<0.001
13	G36198	0.07	0.002
14	G36199	0.10	0.003
15	G36200	0.18	0.005
16	G36201	0.14	0.004
17	G36202	0.31	0.009
18	G36203	0.11	0.003
19	G36204	1.88	0.055
20	G36205	0.11	0.003
21	G36206	0.06	0.002
22	G36207	0.86	0.025
23	G36208	0.21	0.006
24	G36209	0.21	0.006
25	G36210	0.51	0.015
26	G36211	0.17	0.005
27	G36212	0.15	0.004

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 2-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G36213	0.16	0.005
29	G36214	0.34	0.010
30	G36215	0.21	0.006
31	G36216	0.18	0.005
32	G36217	0.40	0.012
33	G36218	0.34	0.010
34	G36219	0.28	0.008
35	G36220	0.11	0.003

QC DATA:

Repeat:

1	G36186	0.54	0.016
10	G36195	0.23	0.007
20	G36205	0.10	0.003

Resplits:

1	G36186	0.36	0.010

Standard:

SI25		1.82	0.053

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

31-Jul-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5439

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07015
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36186	4.2	1.11	20	120	10	5.40	4	13	53	1444	3.32	<10	0.60	1787	37	0.02	6	1060	480	<5	<20	200	0.02	<10	177	<10	6	194
2	G36187	2.8	1.00	15	135	<5	5.63	3	13	54	1365	3.31	<10	0.60	1725	17	0.03	6	1040	116	<5	<20	228	0.03	<10	190	<10	6	147
3	G36188	2.6	0.88	10	115	<5	4.34	4	13	72	1936	3.36	<10	0.51	1213	23	0.04	6	960	108	<5	<20	214	0.02	<10	197	<10	6	105
4	G36189	9.0	0.96	10	125	30	4.82	4	14	53	1041	3.34	<10	0.51	1198	4	0.05	5	1020	686	<5	<20	216	0.03	<10	277	<10	4	162
5	G36190	5.8	1.10	20	115	25	4.64	3	14	61	1508	3.49	10	0.65	1530	7	0.03	8	870	134	<5	<20	210	0.02	<10	239	<10	6	98
6	G36191	2.2	1.15	20	110	<5	5.29	3	14	60	1766	3.46	10	0.74	1657	18	0.03	14	900	50	<5	<20	216	0.02	<10	192	<10	9	86
7	G36192	4.6	1.28	30	125	35	6.01	4	13	61	1265	4.33	20	1.06	1992	19	0.04	20	830	122	<5	<20	282	0.04	<10	235	<10	11	113
8	G36193	2.8	1.46	30	135	15	5.36	5	14	53	1002	5.47	10	1.30	2185	25	0.03	23	890	68	<5	<20	215	0.04	<10	392	<10	10	140
9	G36194	4.0	1.08	15	100	<5	4.68	5	18	62	3234	5.10	10	0.76	1739	14	0.03	16	1070	44	<5	<20	210	0.02	<10	224	<10	8	101
10	G36195	2.6	1.31	25	115	<5	3.93	6	21	79	1843	6.69	10	0.93	1570	36	0.02	31	1110	206	<5	<20	188	0.04	<10	236	<10	9	124
11	G36196	5.6	1.45	20	140	20	3.88	6	23	85	1270	5.84	20	1.26	1625	17	0.03	50	1770	250	<5	<20	213	0.07	<10	241	<10	10	184
12	G36197	<0.2	1.13	5	275	<5	0.61	2	9	93	4	2.40	<10	0.61	560	1	0.13	7	810	8	<5	<20	87	0.15	<10	47	<10	5	50
13	G36198	9.8	1.35	20	130	45	4.48	9	17	77	1179	5.05	20	1.19	1563	29	0.05	26	1400	416	<5	<20	247	0.08	<10	193	<10	10	350
14	G36199	4.0	0.71	15	90	15	3.47	3	18	73	718	3.45	20	0.46	1119	33	0.06	25	1060	266	<5	<20	186	0.03	<10	95	<10	11	67
15	G36200	2.8	0.81	25	90	5	3.71	4	15	88	813	4.43	20	0.57	1355	10	0.06	25	1100	100	<5	<20	196	0.03	<10	153	<10	10	86
16	G36201	3.0	0.96	15	105	<5	4.74	4	19	77	1285	4.30	20	0.82	1632	18	0.06	24	1090	108	<5	<20	240	0.05	<10	180	<10	11	119
17	G36202	3.4	0.91	15	110	10	3.42	4	15	85	945	4.64	20	0.69	1409	37	0.04	20	1150	130	<5	<20	217	0.04	<10	234	<10	8	115
18	G36203	2.8	0.91	30	100	15	3.31	5	14	82	702	4.82	20	0.69	1721	72	0.02	12	600	96	<5	<20	188	0.02	<10	201	<10	6	126
19	G36204	4.2	1.16	40	80	<5	1.12	7	24	64	8631	4.46	20	0.61	212	646	0.05	84	170	60	15	<20	80	0.04	<10	43	<10	9	88
20	G36205	5.4	0.82	15	110	50	4.17	7	13	81	688	6.02	20	0.62	1537	58	0.02	15	540	164	<5	<20	254	0.02	<10	305	<10	7	148
21	G36206	1.2	0.84	10	120	<5	2.02	2	7	85	304	2.05	20	0.62	633	37	0.08	25	1260	80	<5	<20	130	0.08	<10	125	<10	10	99
22	G36207	7.8	1.18	20	110	5	3.19	8	17	82	2858	5.73	20	0.86	1158	12	0.04	28	1540	294	<5	<20	207	0.10	<10	224	<10	13	337
23	G36208	2.2	0.95	15	105	<5	3.00	4	15	81	1051	4.50	10	0.77	1027	22	0.05	24	1090	62	<5	<20	200	0.06	<10	206	<10	10	127
24	G36209	2.4	1.01	15	110	<5	3.49	4	14	104	984	3.85	10	0.68	1177	56	0.03	29	1100	82	<5	<20	225	0.07	<10	201	<10	10	104
25	G36210	2.8	1.26	25	110	<5	3.27	6	24	82	1566	6.74	<10	0.92	1480	42	0.02	23	740	90	<5	<20	234	0.05	<10	318	<10	7	170

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36211	3.0	1.13	30	115	<5	2.55	4	14	65	1306	3.69	10	0.67	1012	20	0.04	17	1120	144	<5	<20	163	0.07	<10	159	<10	7	109
27	G36212	1.8	1.28	30	120	<5	3.33	4	16	68	778	3.65	10	0.79	1225	23	0.03	23	1110	52	<5	<20	195	0.09	<10	123	<10	9	74
28	G36213	2.4	0.89	30	85	<5	3.37	4	17	62	1253	4.17	10	0.40	1191	45	0.04	20	1340	116	<5	<20	209	0.07	<10	89	<10	11	71
29	G36214	3.8	0.82	40	105	5	4.07	5	12	60	576	4.20	10	0.50	1625	15	0.03	9	1190	244	<5	<20	254	0.04	<10	106	<10	8	122
30	G36215	3.2	0.95	45	110	5	3.09	5	13	66	333	4.39	10	0.63	1392	28	0.04	7	1190	294	<5	<20	194	0.05	<10	107	<10	7	161
31	G36216	2.8	0.92	40	115	10	3.36	4	14	59	297	4.16	10	0.63	1551	31	0.04	7	1180	292	<5	<20	215	0.05	<10	104	<10	6	138
32	G36217	6.4	0.55	50	90	10	3.45	6	10	71	734	3.64	<10	0.30	2509	5	0.02	7	630	194	<5	<20	216	0.03	<10	94	<10	4	282
33	G36218	7.2	0.97	50	115	<5	7.09	5	12	55	2158	5.64	10	0.78	5249	2	0.02	12	880	38	<5	<20	472	0.05	<10	653	<10	6	135
34	G36219	5.0	0.88	35	105	<5	6.26	4	10	62	896	4.48	10	0.55	4133	2	0.02	10	1030	30	<5	<20	390	0.03	<10	491	<10	6	100
35	G36220	2.4	0.97	30	90	<5	5.18	3	8	67	691	3.34	10	0.61	3004	3	0.04	10	1250	16	<5	<20	365	0.02	<10	321	<10	6	102
QC DATA:																													
Repeat:																													
1	G36186	4.0	1.01	20	135	5	5.25	4	14	56	1442	3.50	<10	0.62	1804	36	0.02	6	1070	472	<5	<20	213	0.02	<10	189	<10	6	180
10	G36195	2.9	1.33	25	120	<5	3.86	7	21	81	1823	6.79	10	0.94	1537	35	0.02	32	1120	210	<5	<20	190	0.04	<10	250	<10	9	123
Resplit:																													
1	G36186	3.9	1.01	25	145	<5	5.36	4	15	63	1480	3.83	<10	0.60	1847	33	0.02	6	1070	446	<5	<20	219	0.03	<10	203	<10	7	196
Standard:																													
Pb113		11.4	0.28	65	65	<5	1.77	55	2	5	2416	1.16	<10	0.11	1540	61	0.02	<1	80	5494	5	<20	78	0.01	<10	7	<10	<1	7154

Aqua Regia Digestion
ICP Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
dl/5437
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007-5442

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

2-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07016
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34166	0.39	0.011
2	G34167	0.70	0.020
3	G34168	0.31	0.009
4	G34169	0.44	0.013
5	G34170	0.58	0.017
6	G34171	0.52	0.015
7	G34172	0.67	0.020
8	G34173	0.66	0.019
9	G34174	0.55	0.016
10	G34175	0.61	0.018
11	G34176	0.50	0.015
12	G34177	0.74	0.022
13	G34178	0.60	0.017
14	G34179	0.37	0.011
15	G34180	0.71	0.021
16	G34181	0.62	0.018
17	G34182	0.43	0.013
18	G34183	0.66	0.019
19	G34184	0.52	0.015
20	G34185	0.74	0.022
21	G34186	0.52	0.015
22	G34187	0.55	0.016
23	G34188	0.87	0.025
24	G34189	0.64	0.019
25	G34190	0.92	0.027
26	G34191	0.47	0.014
27	G34192	<0.03	<0.001

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 2-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G34193	0.54	0.016
29	G34194	0.44	0.013
30	G34195	0.56	0.016
31	G34196	0.49	0.014
32	G34197	0.46	0.013
33	G34198	0.73	0.021
34	G34199	0.56	0.016
35	G34200	0.55	0.016

QC DATA:

Repeat:

1	G34166	0.39	0.011
2	G34167	0.78	0.023
5	G34170	0.57	0.017
10	G34175	0.66	0.019
19	G34184	0.53	0.015
25	G34190	1.09	0.032
33	G34198	0.78	0.023

Resplits:

1	G34166	0.41	0.012

Standard:

SI25	1.82	0.053
S125	1.83	0.053
SJ32	2.64	0.077

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

3-[illegible]-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5442

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Sample Type: Core
Project: KSM
Shipment #: 07016
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34166	<0.2	1.04	15	30	<5	1.87	2	5	104	963	2.82	<10	0.63	804	15	0.04	2	1090	54	<5	<20	136	<0.01	<10	15	<10	7	152
2	G34167	0.8	1.08	15	30	<5	0.60	2	6	88	2609	3.16	<10	0.66	481	16	0.04	<1	1020	66	<5	<20	56	<0.01	<10	18	<10	3	142
3	G34168	3.0	1.27	30	40	<5	0.99	2	15	60	2687	3.41	20	0.61	176	216	0.05	11	610	60	10	<20	59	0.04	<10	40	<10	8	282
4	G34169	<0.2	1.23	15	40	<5	1.16	1	5	65	1228	2.73	<10	0.75	859	18	0.04	<1	1070	30	<5	<20	76	<0.01	<10	19	<10	4	168
5	G34170	<0.2	1.15	15	30	<5	0.38	<1	6	92	1742	2.95	<10	0.66	394	18	0.03	<1	1070	48	<5	<20	44	<0.01	<10	18	<10	3	162
6	G34171	<0.2	1.11	15	35	<5	0.89	<1	6	76	1695	2.93	<10	0.63	673	12	0.04	1	1060	32	<5	<20	70	<0.01	<10	19	<10	4	124
7	G34172	<0.2	1.05	10	40	<5	1.17	<1	6	81	1793	2.60	<10	0.57	751	14	0.03	<1	970	30	<5	<20	89	<0.01	<10	16	<10	4	167
8	G34173	<0.2	0.92	10	40	<5	0.96	2	5	74	1942	2.74	<10	0.45	674	11	0.03	<1	1030	44	<5	<20	80	<0.01	<10	18	<10	4	185
9	G34174	<0.2	0.93	10	30	<5	1.36	1	5	87	1806	2.91	<10	0.53	896	9	0.03	<1	860	42	<5	<20	103	<0.01	<10	15	<10	4	164
10	G34175	0.8	1.12	15	30	<5	0.89	1	8	53	1962	3.80	<10	0.54	586	8	0.04	<1	1010	26	<5	<20	66	<0.01	<10	20	<10	4	175
11	G34176	0.3	0.99	15	30	<5	1.28	1	6	75	1350	3.10	<10	0.51	828	11	0.03	<1	1050	30	<5	<20	77	<0.01	<10	16	<10	5	167
12	G34177	<0.2	1.00	10	40	<5	1.29	1	6	73	1577	2.74	<10	0.53	827	12	0.03	<1	1010	28	<5	<20	121	<0.01	<10	17	<10	4	131
13	G34178	0.6	1.11	10	45	<5	0.87	<1	6	80	1408	3.15	<10	0.59	579	11	0.04	<1	1090	28	<5	<20	56	<0.01	<10	24	<10	4	137
14	G34179	<0.2	1.10	15	45	<5	1.29	2	5	54	1419	2.80	<10	0.65	765	14	0.04	1	1080	22	<5	<20	99	<0.01	<10	21	<10	5	205
15	G34180	0.2	0.91	10	25	<5	0.97	2	6	59	2602	2.74	<10	0.52	628	16	0.04	<1	930	18	<5	<20	78	<0.01	<10	17	<10	4	182
16	G34181	1.1	0.68	10	25	<5	1.52	2	6	65	2374	2.91	<10	0.45	823	21	0.02	<1	950	36	5	<20	81	<0.01	<10	8	<10	5	108
17	G34182	0.4	0.78	10	25	<5	1.59	1	6	90	1352	2.65	<10	0.48	851	15	0.02	1	1040	26	<5	<20	81	<0.01	<10	11	<10	4	94
18	G34183	2.7	0.46	15	25	<5	1.22	1	7	103	2562	3.37	<10	0.41	1279	13	0.02	<1	940	34	5	<20	29	<0.01	<10	6	<10	3	72
19	G34184	2.3	0.44	140	25	<5	0.30	2	7	122	3778	3.90	<10	0.13	272	8	0.03	<1	900	56	100	<20	11	<0.01	<10	6	<10	2	180
20	G34185	<0.2	0.63	15	30	<5	1.45	3	5	93	2403	2.86	<10	0.52	1124	49	0.02	<1	900	104	5	<20	31	<0.01	<10	8	<10	4	288
21	G34186	<0.2	0.79	10	30	<5	3.39	1	6	89	2417	2.49	<10	0.56	1466	11	0.02	<1	840	54	<5	<20	172	<0.01	<10	8	<10	4	70
22	G34187	0.9	0.49	10	25	<5	0.81	<1	6	89	2541	2.53	<10	0.20	365	13	0.02	<1	1010	32	<5	<20	29	<0.01	<10	7	<10	3	40
23	G34188	<0.2	0.75	10	25	<5	0.68	<1	6	78	2669	3.13	<10	0.42	449	16	0.02	<1	970	32	<5	<20	25	<0.01	<10	7	<10	3	93
24	G34189	0.2	0.55	10	30	<5	2.14	<1	6	66	1590	2.18	<10	0.47	1044	14	0.02	<1	1040	22	<5	<20	153	<0.01	<10	11	<10	4	63
25	G34190	0.4	0.69	10	25	<5	1.24	3	8	110	3134	3.34	<10	0.35	425	14	0.03	<1	760	42	<5	<20	103	<0.01	<10	13	<10	2	95
26	G34191	<0.2	0.69	10	20	<5	0.85	<1	6	103	2430	2.96	<10	0.35	356	22	0.03	<1	930	34	<5	<20	50	<0.01	<10	11	<10	3	84
27	G34192	<0.2	1.28	10	225	<5	0.48	<1	5	124	4	1.95	<10	0.57	494	<1	0.09	6	910	6	<5	<20	80	0.13	<10	42	<10	5	58
28	G34193	0.4	0.68	15	25	<5	1.24	<1	6	93	2934	2.94	<10	0.38	500	20	0.02	<1	890	50	5	<20	47	<0.01	<10	8	<10	3	79
29	G34194	2.1	0.61	10	25	<5	2.56	<1	6	83	1860	2.57	<10	0.33	809	26	0.02	<1	850	26	<5	<20	141	<0.01	<10	8	<10	3	58
30	G34195	<0.2	0.78	10	25	<5	1.57	<1	6	67	1481	2.56	<10	0.49	848	17	0.02	<1	970	14	<5	<20	122	<0.01	<10	10	<10	3	74

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
31	G34196	10.8	0.95	10	35	<5	2.54	<1	5	56	1285	2.64	<10	0.58	694	22	0.03	<1	980	24	<5	<20	297	<0.01	<10	14	<10	4	124
32	G34197	1.5	0.84	10	25	<5	1.88	1	7	45	1549	3.03	<10	0.42	753	26	0.03	<1	1050	30	<5	<20	151	<0.01	<10	11	<10	3	123
33	G34198	2.3	0.83	10	25	<5	1.45	1	9	76	2175	3.19	<10	0.48	764	18	0.02	<1	1010	26	<5	<20	82	<0.01	<10	11	<10	4	85
34	G34199	2.7	1.07	30	35	<5	2.20	1	6	62	1856	3.00	<10	0.76	920	22	0.03	<1	1020	24	10	<20	207	<0.01	<10	15	<10	4	123
35	G34200	1.4	0.72	35	25	<5	1.12	1	7	89	2028	3.49	<10	0.44	591	13	0.03	<1	1060	32	15	<20	76	<0.01	<10	9	<10	4	118
QC DATA:																													
Repeat:																													
1	G34166	<0.2	1.01	15	25	<5	1.74	1	5	101	969	2.75	<10	0.61	789	14	0.04	1	1030	50	<5	<20	127	<0.01	<10	15	<10	6	147
10	G34175	0.9	1.09	15	25	<5	0.88	1	8	51	1962	3.75	<10	0.53	587	8	0.04	<1	1000	28	<5	<20	64	<0.01	<10	20	<10	4	176
19	G34184	2.1	0.40	140	25	<5	0.31	2	6	114	3670	3.87	<10	0.13	274	8	0.03	<1	880	54	100	<20	10	<0.01	<10	5	<10	2	173
Resplit:																													
1	G34166	0.2	0.88	10	25	<5	1.94	1	5	67	1027	2.78	<10	0.62	840	13	0.03	<1	990	62	<5	<20	124	<0.01	<10	12	<10	7	145
Standard:																													
Pb113		11.6	0.32	40	55	<5	1.61	37	2	3	2371	0.90	<10	0.10	1472	79	0.02	<1	80	5580	15	<20	77	<0.01	<10	6	<10	1	6985

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl/
d:/N7158
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007-5449

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

09-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07017
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36221	0.12	0.003
2	G36222	0.18	0.005
3	G36223	0.14	0.004
4	G36224	0.10	0.003
5	G36225	0.25	0.007
6	G36226	0.71	0.021
7	G36227	0.66	0.019
8	G36228	0.95	0.028
9	G36229	0.60	0.017
10	G36230	0.95	0.028
11	G36231	0.62	0.018
12	G36232	1.82	0.053
13	G36233	0.86	0.025
14	G36234	0.89	0.026
15	G36235	0.54	0.016
16	G36236	0.29	0.008
17	G36237	0.65	0.019
18	G36238	0.34	0.010
19	G36239	0.66	0.019
20	G36240	0.58	0.017
21	G36241	<0.03	<0.001
22	G36242	0.41	0.012
23	G36243	0.47	0.014
24	G36244	0.47	0.014
25	G36245	1.01	0.029

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5449 09-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	G36246	0.45	0.013
27	G36247	1.30	0.038
28	G36248	0.58	0.017
29	G36249	0.55	0.016
30	G36250	0.29	0.008
31	G36251	0.20	0.006
32	G36252	0.44	0.013
33	G36253	0.41	0.012
34	G36254	0.21	0.006
35	G36255	0.27	0.008

QC DATA:

Repeat:

1	G36221	0.13	0.004
10	G36230	0.86	0.025
12	G36232	1.71	0.050
13	G36233	0.82	0.024
19	G36239	0.65	0.019
20	G36240	0.58	0.017
25	G36245	1.04	0.030
26	G36246	0.46	0.013
27	G36247	1.31	0.038
28	G36248	0.63	0.018

Resplit:

1	G36221	0.12	0.003

Standard:

S125		1.82	0.053
S125		1.81	0.053
SJ32		2.65	0.077

JJ/bp
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

09 1-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5449

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07017
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36221	1.4	0.17	15	45	<5	2.15	<1	4	63	179	1.56	<10	0.01	1097	3	0.02	4	100	18	<5	<20	130	0.02	<10	16	<10	<1	3
2	G36222	2.3	0.29	10	50	<5	3.21	<1	4	61	403	1.62	<10	0.07	1555	7	0.03	4	100	24	<5	<20	243	0.03	<10	43	<10	<1	11
3	G36223	2.7	0.61	15	80	<5	3.41	<1	4	63	732	1.81	<10	0.33	1772	11	0.03	6	440	26	10	<20	344	0.03	<10	123	<10	1	44
4	G36224	2.7	0.33	10	55	<5	4.43	<1	7	46	1228	1.71	<10	0.18	2122	7	0.02	4	820	42	<5	<20	483	0.03	<10	50	<10	4	27
5	G36225	4.8	0.23	10	60	<5	4.50	1	12	70	1551	2.50	<10	0.34	2140	34	<0.01	13	640	176	10	<20	431	0.03	<10	16	<10	9	23
6	G36226	2.3	0.22	5	40	<5	0.69	<1	9	95	1969	2.77	<10	0.16	317	39	<0.01	6	590	18	<5	<20	59	0.02	<10	5	<10	1	27
7	G36227	2.7	0.22	<5	35	<5	0.22	2	7	136	2660	3.26	<10	0.06	194	84	<0.01	6	300	32	<5	<20	21	0.01	<10	4	<10	<1	56
8	G36228	1.8	0.30	5	35	<5	0.24	1	10	137	1712	3.06	<10	0.12	273	76	<0.01	6	460	24	<5	<20	15	0.02	<10	5	<10	<1	42
9	G36229	2.6	0.25	10	35	<5	0.16	2	10	128	2161	3.24	<10	0.09	155	45	<0.01	6	460	38	5	<20	17	0.01	<10	4	<10	<1	76
10	G36230	2.5	0.49	10	40	<5	0.57	1	11	122	2135	3.18	<10	0.30	477	35	<0.01	5	580	34	<5	<20	35	0.02	<10	8	<10	<1	71
11	G36231	2.2	0.33	10	40	<5	0.59	2	7	152	2214	3.08	<10	0.17	434	52	<0.01	8	390	26	10	<20	36	0.01	<10	6	<10	<1	53
12	G36232	2.2	0.20	<5	30	<5	0.09	2	6	155	1992	3.50	<10	0.05	89	35	<0.01	7	250	40	<5	<20	8	0.02	<10	5	<10	<1	100
13	G36233	1.9	0.30	<5	50	<5	0.07	3	6	173	2135	2.85	<10	0.13	156	35	0.01	6	220	38	<5	<20	9	0.01	<10	6	<10	<1	108
14	G36234	2.1	0.60	<5	45	<5	0.12	1	11	148	2295	3.54	<10	0.35	432	50	0.01	7	430	26	5	<20	10	0.02	<10	11	<10	<1	65
15	G36235	3.3	0.24	15	35	<5	0.20	2	10	131	1451	3.26	<10	0.07	148	52	0.01	9	680	42	<5	<20	10	0.02	<10	5	<10	<1	122
16	G36236	3.1	1.08	35	55	<5	0.96	2	21	51	2635	3.32	10	0.61	194	177	0.03	9	490	60	15	<20	54	0.04	<10	40	<10	5	258
17	G36237	6.5	0.16	30	40	<5	0.22	21	10	100	2336	4.03	<10	<0.01	61	50	0.01	16	790	40	5	<20	16	0.02	<10	7	<10	<1	1436
18	G36238	4.2	0.19	20	40	<5	0.81	2	13	158	1159	3.41	<10	0.04	393	116	<0.01	22	820	22	<5	<20	32	0.02	<10	7	<10	<1	79
19	G36239	3.5	0.24	30	40	<5	0.59	2	14	137	1676	4.39	<10	0.05	282	68	<0.01	17	790	18	<5	<20	31	0.02	<10	7	<10	<1	40
20	G36240	3.5	0.47	20	45	<5	1.42	4	11	122	1442	3.44	<10	0.32	939	111	<0.01	14	480	70	5	<20	70	0.03	<10	7	<10	1	161
21	G36241	<0.2	0.94	10	245	15	0.55	<1	7	96	6	2.10	<10	0.60	513	1	0.10	7	920	20	10	<20	83	0.09	<10	41	<10	2	41
22	G36242	2.1	0.40	10	50	<5	0.50	1	12	109	1626	2.96	<10	0.22	409	138	<0.01	15	520	28	15	<20	26	0.01	<10	7	<10	<1	40
23	G36243	2.5	0.40	15	50	<5	0.70	<1	15	99	1684	3.20	<10	0.22	682	57	<0.01	15	460	32	<5	<20	35	0.02	<10	6	<10	<1	46
24	G36244	3.1	0.89	20	50	<5	0.91	<1	19	124	1329	3.80	<10	0.54	1433	39	<0.01	25	730	30	5	<20	34	0.03	<10	17	<10	<1	124
25	G36245	8.7	1.10	265	50	<5	0.91	2	18	91	886	5.42	<10	0.68	1564	59	0.01	23	2570	54	15	<20	28	0.04	<10	31	<10	<1	331

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36246	6.1	0.53	30	45	<5	0.25	2	15	114	1388	4.70	<10	0.33	516	26	<0.01	22	710	42	5	<20	13	0.03	<10	9	<10	<1	132
27	G36247	4.8	0.74	165	50	<5	1.22	1	15	121	1756	4.38	<10	0.53	1482	49	<0.01	16	980	46	10	<20	38	0.03	<10	16	<10	<1	176
28	G36248	1.4	0.73	30	50	<5	1.66	1	14	101	1451	3.78	<10	0.48	1451	115	0.01	17	690	44	10	<20	62	0.03	<10	12	<10	2	68
29	G36249	1.3	0.44	5	45	<5	1.18	1	12	120	1658	3.33	<10	0.25	765	85	0.01	14	350	36	<5	<20	48	0.02	<10	7	<10	<1	51
30	G36250	2.1	0.18	15	40	<5	0.82	2	10	145	1515	2.97	<10	0.03	458	221	0.01	12	230	68	<5	<20	38	0.02	<10	3	<10	<1	81
31	G36251	1.4	0.28	15	40	<5	0.52	<1	11	134	1308	2.45	<10	0.14	412	12	0.01	11	310	34	<5	<20	27	0.02	<10	4	<10	<1	44
32	G36252	1.7	0.56	20	45	<5	0.89	6	14	112	1415	3.52	<10	0.30	858	44	<0.01	18	760	74	5	<20	41	0.03	<10	9	<10	2	285
33	G36253	1.9	0.52	25	55	<5	0.51	2	16	98	2388	3.31	<10	0.27	531	50	<0.01	20	800	42	15	<20	32	0.01	<10	9	<10	<1	85
34	G36254	1.4	0.69	20	60	<5	0.50	<1	17	76	853	3.07	<10	0.31	397	78	<0.01	26	2110	30	10	<20	23	0.02	<10	12	<10	3	82
35	G36255	1.7	0.40	15	55	<5	0.70	2	13	103	1000	2.63	<10	0.16	427	53	<0.01	24	1270	56	10	<20	37	0.02	<10	13	<10	3	91
QC DATA:																													
Repeat:																													
1	G36221	1.4	0.17	15	45	<5	2.12	<1	5	61	179	1.53	<10	0.01	1082	2	0.02	3	100	18	<5	<20	129	0.02	<10	15	<10	<1	3
10	G36230	2.5	0.49	<5	35	<5	0.58	2	12	123	2153	3.23	<10	0.30	482	35	<0.01	6	590	36	<5	<20	34	0.02	<10	8	<10	<1	72
19	G36239	3.5	0.25	35	55	<5	0.59	2	14	137	1702	4.43	<10	0.05	286	64	<0.01	16	790	18	<5	<20	30	0.03	<10	8	<10	<1	41
Resplit:																													
1	G36221	1.3	0.16	15	40	<5	2.11	<1	4	61	180	1.44	<10	0.02	1073	2	0.02	4	100	16	<5	<20	129	0.02	<10	15	<10	<1	3
Standard:																													
Pb113		11.0	0.20	45	65	<5	1.65	34	2	5	2326	1.10	<10	0.02	1567	62	0.02	<1	80	5538	10	<20	87	0.02	<10	6	10	<1	6964

Aqua Regia Digestion
ICP Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/bp
df/5449
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007-5450

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

2-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07019
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36256	0.55	0.016
2	G36257	0.58	0.017
3	G36258	0.23	0.007
4	G36259	0.46	0.013
5	G36260	0.33	0.010
6	G36261	0.33	0.010
7	G36262	0.27	0.008
8	G36263	0.12	0.003
9	G36264	1.07	0.031
10	G36265	0.23	0.007
11	G36266	0.23	0.007
12	G36267	0.08	0.002
13	G36268	0.08	0.002
14	G36269	0.24	0.007
15	G36270	0.26	0.008
16	G36271	0.21	0.006
17	G36272	0.15	0.004
18	G36273	0.17	0.005
19	G36274	0.33	0.010
20	G36275	0.42	0.012
21	G36276	0.36	0.010
22	G36277	0.12	0.003
23	G36278	0.24	0.007
24	G36279	0.27	0.008
25	G36280	<0.03	<0.001
26	G36281	0.23	0.007
27	G36282	0.21	0.006

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AW2007-5450 2-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G36283	0.13	0.004
29	G36284	0.17	0.005
30	G36285	0.15	0.004
31	G36286	0.26	0.008
32	G36287	0.16	0.005
33	G36288	0.15	0.004
34	G36289	0.13	0.004
35	G36290	0.08	0.002

QC DATA:

Repeat:

1	G36256	0.53	0.015
10	G36265	0.20	0.006
19	G36274	0.33	0.010

Resplits:

1	G36256	0.58	0.017

Standard:

SI25		1.81	0.053

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5450

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07019
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36256	1.9	0.96	5	35	<5	1.07	<1	11	87	1266	3.51	<10	0.57	917	78	<0.01	9	1030	34	<5	<20	49	0.03	<10	17	<10	4	57
2	G36257	1.5	0.95	15	40	<5	1.61	1	14	87	1127	3.64	<10	0.59	1201	160	<0.01	6	1010	90	<5	<20	68	0.03	<10	22	<10	5	93
3	G36258	1.1	1.10	10	40	<5	2.58	2	15	97	935	3.64	<10	0.85	1703	26	<0.01	4	930	72	<5	<20	110	0.04	<10	30	<10	5	132
4	G36259	1.7	1.16	<5	40	<5	2.07	<1	14	98	1267	3.73	<10	0.92	1089	44	<0.01	5	900	42	<5	<20	111	0.03	<10	32	<10	3	55
5	G36260	1.1	1.15	15	50	<5	1.10	<1	14	105	1122	3.68	<10	0.76	717	39	<0.01	4	1010	82	<5	<20	53	0.03	<10	28	<10	3	70
6	G36261	1.0	1.09	5	40	<5	1.51	<1	21	132	1262	4.03	<10	0.79	722	42	<0.01	6	800	30	<5	<20	90	0.03	<10	29	<10	3	47
7	G36262	0.8	1.10	10	45	<5	1.70	<1	13	81	935	3.35	<10	0.83	673	66	<0.01	5	1010	32	<5	<20	107	0.03	<10	29	<10	5	61
8	G36263	0.6	1.28	<5	60	<5	1.72	<1	13	64	808	3.48	<10	0.96	843	18	<0.01	4	1130	32	<5	<20	99	0.03	<10	36	<10	4	73
9	G36264	3.3	1.17	55	60	<5	0.72	3	16	59	3311	4.05	20	0.50	270	215	0.03	13	340	126	25	<20	28	0.05	<10	44	<10	5	157
10	G36265	0.7	0.99	<5	35	<5	0.98	<1	16	75	1018	3.55	<10	0.67	487	44	<0.01	5	1150	28	<5	<20	56	0.02	<10	30	<10	5	56
11	G36266	0.8	0.99	<5	35	<5	0.87	<1	16	89	1294	3.40	<10	0.67	470	47	<0.01	5	1100	28	<5	<20	49	0.02	<10	30	<10	5	56
12	G36267	0.6	1.17	10	50	<5	1.05	<1	11	89	724	3.27	<10	0.94	574	38	<0.01	4	1050	24	<5	<20	55	0.02	<10	37	<10	3	65
13	G36268	0.6	1.20	5	55	<5	1.09	<1	11	86	644	3.31	<10	0.92	656	24	<0.01	4	1050	22	<5	<20	52	0.03	<10	32	<10	2	56
14	G36269	1.7	1.16	25	35	<5	1.61	<1	22	88	1202	4.72	<10	0.90	943	16	<0.01	11	1480	34	<5	<20	63	0.04	<10	36	<10	3	81
15	G36270	1.0	0.61	<5	30	<5	1.07	<1	15	109	1272	3.00	<10	0.32	635	29	<0.01	16	590	34	<5	<20	44	0.02	<10	8	<10	4	44
16	G36271	0.7	1.00	5	50	<5	1.62	<1	15	83	1049	3.76	<10	0.72	1134	27	<0.01	20	570	28	<5	<20	60	0.03	<10	12	<10	3	58
17	G36272	0.6	0.78	<5	40	<5	1.58	<1	15	147	1072	3.35	<10	0.48	926	23	<0.01	17	520	32	<5	<20	53	0.03	<10	11	<10	2	52
18	G36273	1.0	1.05	25	35	<5	1.27	<1	24	120	1314	5.06	<10	0.67	1006	54	<0.01	26	600	62	<5	<20	50	0.04	<10	16	<10	1	94
19	G36274	1.1	1.03	30	35	<5	1.35	2	16	127	1245	3.82	<10	0.73	886	72	<0.01	21	780	28	<5	<20	57	0.03	<10	21	<10	2	322
20	G36275	1.1	0.43	<5	35	<5	1.09	<1	12	115	1509	2.70	<10	0.21	353	51	<0.01	13	360	30	<5	<20	60	0.02	<10	8	<10	1	34
21	G36276	0.9	0.58	<5	30	<5	1.13	<1	13	110	1440	3.06	<10	0.40	378	13	<0.01	12	300	28	<5	<20	63	0.02	<10	13	<10	<1	30
22	G36277	0.5	0.63	10	45	<5	1.16	1	10	134	896	2.24	<10	0.49	433	11	<0.01	10	210	34	<5	<20	61	0.02	<10	9	<10	<1	84
23	G36278	0.9	1.09	10	60	<5	1.33	<1	13	119	999	2.98	<10	0.90	564	17	<0.01	16	650	30	<5	<20	82	0.02	<10	31	<10	4	78
24	G36279	1.3	1.29	<5	40	<5	1.50	<1	20	91	1097	4.09	<10	1.14	670	61	<0.01	20	830	40	<5	<20	99	0.03	<10	37	<10	6	74
25	G36280	<0.2	1.05	5	250	25	0.60	<1	6	128	6	2.32	<10	0.60	551	2	0.10	7	700	18	<5	<20	84	0.14	<10	47	<10	2	44

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36281	1.0	0.83	10	30	<5	1.29	<1	14	117	1117	3.04	<10	0.60	496	43	<0.01	17	540	30	<5	<20	95	0.02	<10	24	<10	3	34
27	G36282	1.3	0.82	<5	30	<5	3.69	3	17	118	1042	4.13	<10	0.70	1159	69	<0.01	14	380	96	<5	<20	178	0.04	<10	17	<10	3	119
28	G36283	0.7	0.80	10	45	<5	3.96	<1	12	100	762	3.13	<10	0.59	1307	92	<0.01	13	530	28	<5	<20	178	0.03	<10	16	<10	4	56
29	G36284	1.1	0.94	15	45	<5	2.61	<1	19	89	1006	3.58	<10	0.71	942	36	<0.01	28	1370	34	<5	<20	144	0.05	<10	24	<10	6	52
30	G36285	1.7	0.83	5	40	<5	3.44	<1	26	95	1169	3.42	<10	0.63	894	35	0.01	29	1350	72	<5	<20	232	0.05	<10	25	<10	5	44
31	G36286	1.2	1.32	10	35	<5	1.56	<1	15	67	1183	4.23	<10	1.14	554	63	0.02	7	1050	26	<5	<20	133	0.05	<10	61	<10	6	44
32	G36287	0.8	1.13	5	50	<5	1.26	<1	12	101	887	3.36	<10	0.95	380	56	0.04	6	920	22	<5	<20	124	0.04	<10	60	<10	5	35
33	G36288	0.9	1.12	5	40	<5	1.32	<1	14	74	965	3.73	<10	0.98	441	19	0.04	5	970	22	<5	<20	118	0.04	<10	62	<10	5	45
34	G36289	0.6	1.21	5	55	<5	1.98	<1	13	75	779	3.38	<10	1.00	609	67	0.03	3	980	22	<5	<20	183	0.05	<10	59	<10	6	48
35	G36290	0.6	1.06	5	45	<5	1.74	<1	11	75	698	3.31	<10	0.95	572	68	0.03	4	1000	24	<5	<20	136	0.04	<10	57	<10	5	47
QC DATA:																													
Repeat:																													
1	G36256	1.9	1.02	10	45	<5	1.09	<1	12	92	1321	3.58	<10	0.60	943	87	<0.01	10	1030	36	<5	<20	57	0.03	<10	19	<10	4	57
10	G36265	0.6	1.01	5	40	<5	0.98	<1	15	78	1009	3.57	<10	0.67	489	45	<0.01	5	1150	28	<5	<20	55	0.02	<10	31	<10	5	56
19	G36274	1.0	1.05	25	35	<5	1.36	2	16	129	1239	3.84	<10	0.74	888	71	<0.01	21	790	28	<5	<20	58	0.03	<10	21	<10	2	327
Resplit:																													
1	G36256	2.0	0.91	10	35	<5	1.07	<1	11	101	1284	3.70	<10	0.52	914	282	<0.01	9	920	34	<5	<20	49	0.03	<10	17	<10	4	51
Standard:																													
Pb113		11.6	0.27	60	60	<5	1.67	38	2	5	2413	1.08	<10	0.10	1427	74	0.02	1	10	5506	10	<20	129	0.02	<10	7	10	<1	6988

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/7163
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007-5451

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

2-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07018
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34201	0.54	0.016
2	G34202	0.73	0.021
3	G34203	1.34	0.039
4	G34204	0.98	0.029
5	G34205	2.50	0.073
6	G34206	0.69	0.020
7	G34207	2.06	0.060
8	G34208	0.76	0.022
9	G34209	0.67	0.020
10	G34210	1.44	0.042
11	G34211	1.07	0.031
12	G34212	<0.03	<0.001
13	G34213	1.32	0.038
14	G34214	0.85	0.025
15	G34215	0.59	0.017
16	G34216	1.42	0.041
17	G34217	0.94	0.027
18	G34218	0.87	0.025
19	G34219	8.40	0.245
20	G34220	3.90	0.114
21	G34221	0.89	0.026
22	G34222	0.70	0.020
23	G34223	0.44	0.013
24	G34224	0.87	0.025
25	G34225	0.05	0.001
26	G34226	1.85	0.054
27	G34227	0.61	0.018

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 2-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G34228	0.62	0.018
29	G34229	0.57	0.017
30	G34230	0.71	0.021
31	G34231	0.52	0.015
32	G34232	1.29	0.038
33	G34233	0.70	0.020
34	G34234	0.81	0.024
35	G34235	0.53	0.015
QC DATA:			
Repeat:			
1	G34201	0.53	0.015
3	G34203	1.45	0.042
5	G34205	2.40	0.070
7	G34207	2.14	0.062
10	G34210	1.32	0.038
19	G34219	8.30	0.242
20	G34220	3.80	0.111
32	G34232	1.32	0.038
33	G34233	0.75	0.022
Resplits:			
1	G34201	0.56	0.016
Standard:			
SJ32		2.68	0.078

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl/jl
XLS/07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5451

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07018
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34201	1.4	1.20	25	130	<5	2.53	<1	9	63	1427	4.01	<10	0.93	1148	15	0.02	2	1050	36	<5	<20	68	0.02	<10	30	<10	1	154
2	G34202	2.1	0.73	25	45	<5	5.42	1	12	66	2019	3.79	<10	0.78	1384	19	0.03	1	940	52	<5	<20	748	0.03	<10	31	<10	4	123
3	G34203	2.4	0.45	55	35	<5	1.80	2	13	67	2236	5.07	<10	0.32	901	15	<0.01	4	960	38	<5	<20	234	0.02	<10	9	<10	1	191
4	G34204	4.5	0.35	75	50	<5	0.41	5	12	73	2499	6.30	<10	0.16	344	11	<0.01	3	870	60	<5	<20	10	0.02	<10	8	<10	<1	434
5	G34205	10.3	0.74	30	55	<5	2.50	7	10	58	3492	3.90	<10	0.77	1716	12	0.01	3	1000	166	<5	<20	61	0.03	<10	14	<10	3	368
6	G34206	2.1	0.92	35	50	<5	1.79	<1	9	88	2423	3.34	<10	0.63	822	16	0.01	3	1060	32	<5	<20	471	0.02	<10	16	<10	2	136
7	G34207	6.1	0.41	80	40	<5	1.02	2	11	101	1950	6.13	<10	0.17	539	14	<0.01	3	890	200	<5	<20	72	0.03	<10	8	<10	<1	92
8	G34208	2.0	0.47	35	45	<5	1.23	<1	12	78	1563	4.55	<10	0.40	706	18	<0.01	2	1050	52	<5	<20	31	0.02	<10	9	<10	<1	83
9	G34209	1.1	1.03	30	70	<5	1.55	<1	9	57	1433	3.50	<10	0.68	934	19	0.01	3	1110	42	<5	<20	60	0.02	<10	17	<10	2	151
10	G34210	1.9	0.78	50	55	<5	0.47	<1	11	54	2003	3.74	<10	0.33	308	13	<0.01	2	1320	60	<5	<20	15	0.01	<10	9	<10	2	187
11	G34211	5.0	0.20	95	25	<5	0.47	2	12	101	1866	4.86	<10	0.03	396	11	<0.01	5	890	90	<5	<20	<1	0.01	<10	6	<10	<1	164
12	G34212	<0.2	0.92	25	255	15	0.60	<1	7	102	4	2.26	<10	0.54	534	2	0.08	5	980	28	<5	<20	64	0.15	<10	44	<10	2	48
13	G34213	13.7	0.20	280	40	<5	0.20	2	8	106	1112	3.67	<10	0.02	92	14	<0.01	4	720	54	40	<20	10	0.01	<10	5	<10	1	132
14	G34214	8.8	0.42	170	35	<5	0.23	2	10	99	1284	4.39	<10	0.23	142	21	<0.01	3	950	42	10	<20	12	0.01	<10	7	<10	1	158
15	G34215	6.7	0.26	155	45	<5	0.29	2	11	79	1515	5.00	<10	0.05	164	12	<0.01	4	1060	48	<5	<20	7	0.02	<10	7	<10	<1	156
16	G34216	7.0	0.71	105	40	<5	0.26	1	12	78	1823	5.04	<10	0.48	288	15	<0.01	3	1050	44	<5	<20	8	0.02	<10	11	<10	<1	183
17	G34217	9.0	0.23	70	45	<5	0.25	3	13	111	2785	6.38	<10	<0.01	142	8	<0.01	4	790	84	<5	<20	13	0.02	<10	6	<10	<1	168
18	G34218	11.8	0.20	90	45	<5	0.27	4	14	111	2558	6.09	<10	<0.01	226	9	<0.01	4	720	126	<5	<20	15	0.02	<10	5	<10	<1	305
19	G34219	28.6	0.17	475	35	<5	0.21	22	7	139	1493	4.69	<10	0.01	247	18	<0.01	4	450	576	100	<20	68	0.02	<10	5	<10	<1	1805
20	G34220	27.3	0.35	400	40	<5	0.26	9	14	110	1919	6.62	<10	0.14	274	14	<0.01	3	740	154	100	<20	23	0.02	<10	7	<10	<1	700
21	G34221	7.1	0.37	60	40	<5	0.39	4	11	105	2129	4.24	<10	0.18	509	8	<0.01	4	840	74	<5	<20	9	0.02	<10	7	<10	<1	304
22	G34222	4.1	1.23	50	60	<5	0.43	1	11	101	1706	3.89	<10	0.82	638	13	<0.01	3	1090	78	<5	<20	17	0.02	<10	14	<10	2	281
23	G34223	3.0	1.88	40	60	<5	0.34	2	12	60	1131	4.88	<10	1.39	677	15	<0.01	2	1170	128	<5	<20	11	0.02	<10	20	<10	<1	560
24	G34224	9.0	1.18	45	50	<5	0.30	9	12	78	2049	4.39	<10	0.83	472	13	<0.01	2	950	164	<5	<20	10	0.02	<10	16	<10	<1	524
25	G34225	0.2	0.96	85	175	30	0.31	<1	80	244	414	>10	<10	0.13	535	116	0.05	470	230	144	<5	<20	<1	0.07	<10	25	<10	<1	437

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34226	9.8	1.01	30	45	<5	0.24	16	14	94	4191	4.39	<10	0.62	298	24	<0.01	5	860	128	<5	<20	8	0.01	<10	12	<10	<1	551
27	G34227	17.0	0.29	90	35	<5	0.41	3	8	96	1773	3.35	<10	0.14	362	24	<0.01	3	930	114	20	<20	23	0.01	<10	7	<10	<1	295
28	G34228	8.0	0.22	85	40	<5	0.49	4	9	98	1594	3.27	<10	0.08	404	16	0.01	3	990	112	5	<20	17	0.01	<10	5	<10	1	300
29	G34229	7.2	0.27	45	35	<5	0.58	4	11	110	2253	3.83	<10	0.13	530	131	0.01	4	840	100	<5	<20	30	0.01	<10	6	<10	<1	210
30	G34230	4.6	0.71	30	45	<5	0.46	5	11	74	1675	3.40	<10	0.50	393	31	0.01	3	1190	156	<5	<20	20	0.01	<10	15	<10	3	602
31	G34231	3.7	0.38	60	40	<5	0.35	12	11	91	1447	4.18	<10	0.16	220	23	0.01	4	1010	120	<5	<20	25	0.01	<10	8	<10	<1	526
32	G34232	0.8	0.53	80	45	<5	0.75	2	11	87	2116	4.02	<10	0.45	712	22	0.01	3	1020	70	<5	<20	51	0.02	<10	10	<10	2	145
33	G34233	0.8	0.89	70	50	<5	0.41	<1	12	83	1544	4.87	<10	0.67	422	21	0.01	3	1070	82	<5	<20	32	0.02	<10	14	<10	1	172
34	G34234	1.1	0.21	90	25	<5	0.44	5	12	116	3010	4.84	<10	0.07	398	16	0.01	4	700	234	15	<20	18	0.01	<10	5	<10	<1	194
35	G34235	4.8	0.69	45	45	<5	0.62	1	12	75	1964	4.88	<10	0.55	660	21	0.01	3	1020	80	<5	<20	30	0.02	<10	14	<10	1	157
QC DATA:																													
Repeat:																													
1	G34201	1.4	1.20	25	135	<5	2.52	<1	9	62	1434	3.98	<10	0.94	1144	14	0.03	2	1050	36	<5	<20	71	0.02	<10	30	<10	2	151
10	G34210	1.9	0.74	45	50	<5	0.46	<1	11	52	1977	3.70	<10	0.32	304	14	<0.01	2	1310	58	<5	<20	15	0.01	<10	9	<10	2	192
19	G34219	28.2	0.16	495	40	<5	0.21	22	7	132	1510	4.71	<10	0.01	250	18	<0.01	4	440	588	100	<20	75	0.02	<10	5	<10	<1	1827
Resplit:																													
1	G34201	1.5	1.21	25	135	<5	2.61	<1	9	70	1459	4.08	<10	0.97	1119	12	0.02	<1	1010	40	<5	<20	71	0.03	<10	31	<10	3	152
Standard:																													
Pb113		11.6	0.24	65	65	<5	1.70	37	2	6	2322	1.10	<10	0.09	1477	80	0.02	2	90	5608	10	<20	69	0.02	<10	8	<10	<1	6943

Aqua Regia Digestion
ICP Finish

JJ/jl
df/1000
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5454

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

3-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07020
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34236	0.60	0.017
2	G34237	0.52	0.015
3	G34238	0.94	0.027
4	G34239	0.60	0.017
5	G34240	0.58	0.017
6	G34241	0.90	0.026
7	G34242	0.60	0.017
8	G34243	0.60	0.017
9	G34244	1.02	0.030
10	G34245	0.69	0.020
11	G34246	<0.03	<0.001
12	G34247	0.68	0.020
13	G34248	0.90	0.026
14	G34249	0.57	0.017
15	G34250	0.77	<0.001
16	G34251	1.06	0.031
17	G34252	0.67	0.020
18	G34253	0.52	0.015
19	G34254	0.71	0.021
20	G34255	1.01	0.029
21	G34256	0.70	0.020
22	G34257	0.58	0.017
23	G34258	0.86	0.025
24	G34259	0.53	0.015

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5454. 3-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
25	G34260	0.53	0.015
26	G34261	0.79	0.023
27	G34262	3.20	0.093
28	G34263	1.34	0.039
29	G34264	0.91	0.027
30	G34265	0.91	0.027
31	G34266	0.61	0.018
32	G34267	0.44	0.013
33	G34268	0.82	0.024
34	G34269	0.69	0.020
35	G34270	0.95	0.028

QC DATA:

Repeat:

1	G34236	0.60	0.017
2	G34237	0.60	0.017
3	G34238	0.97	0.028
6	G34241	0.91	0.027
10	G34245	0.72	0.021
13	G34248	0.87	0.025
16	G34251	1.05	0.031
19	G34254	0.68	0.020
27	G34262	3.30	0.096
35	G34270	1.01	0.029

Resplits:

1	G34236	0.62	0.018

Standard:

S125		1.81	0.053
S125		1.83	0.053
SJ32		2.68	0.078

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/bp
XLS/07

3-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5454

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07020
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34236	11.7	0.29	70	30	<5	0.29	4	9	102	2193	4.35	<10	0.09	182	21	0.01	4	600	174	25	<20	17	0.01	<10	4	<10	<1	184
2	G34237	2.9	0.61	25	35	<5	0.23	<1	9	94	1643	3.79	<10	0.43	180	24	0.01	3	700	44	<5	<20	13	0.01	<10	10	<10	<1	98
3	G34238	2.5	0.79	140	40	<5	0.24	1	11	85	1572	4.31	<10	0.62	214	50	0.01	2	770	36	<5	<20	14	0.02	<10	13	<10	<1	136
4	G34239	3.0	0.76	40	35	<5	0.26	<1	11	87	2038	4.09	<10	0.57	211	30	0.01	2	810	76	<5	<20	12	0.01	<10	13	<10	<1	148
5	G34240	2.8	0.56	5	35	<5	0.15	<1	10	159	2065	4.24	<10	0.31	166	52	0.01	5	390	40	<5	<20	12	0.01	<10	10	<10	<1	75
6	G34241	2.0	0.33	55	40	<5	0.21	1	13	154	1990	5.02	<10	0.07	99	22	0.01	6	590	34	<5	<20	14	0.02	<10	6	<10	<1	37
7	G34242	0.8	1.98	<5	50	<5	0.73	<1	13	142	1234	5.53	<10	1.30	911	65	0.01	5	680	36	<5	<20	48	0.03	<10	32	<10	<1	81
8	G34243	0.8	1.35	<5	45	<5	0.74	1	10	149	1542	4.23	<10	0.89	612	39	0.01	4	600	32	<5	<20	36	0.02	<10	22	<10	<1	56
9	G34244	1.3	1.39	<5	45	<5	1.10	1	13	129	2323	4.48	<10	1.03	607	43	0.01	5	570	60	<5	<20	187	0.02	<10	26	<10	<1	84
10	G34245	1.3	1.78	5	35	<5	2.24	<1	11	65	1858	3.92	<10	1.32	803	52	0.01	2	740	46	<5	<20	286	0.02	<10	20	<10	<1	123
11	G34246	<0.2	0.99	<5	275	<5	0.58	<1	5	103	7	2.00	<10	0.62	552	2	0.09	5	730	16	<5	<20	76	0.13	<10	46	<10	3	44
12	G34247	1.2	2.10	10	65	<5	1.25	<1	12	77	1717	4.15	<10	1.74	1147	54	0.01	2	790	76	<5	<20	169	0.03	<10	23	<10	2	186
13	G34248	1.3	1.63	<5	45	<5	1.45	1	14	79	2244	3.78	<10	1.35	1259	42	0.01	3	750	72	<5	<20	177	0.02	<10	20	<10	1	127
14	G34249	0.8	1.21	<5	45	<5	0.78	<1	12	81	1464	4.23	<10	0.81	642	58	0.01	3	940	48	<5	<20	28	0.02	<10	13	<10	<1	136
15	G34250	1.6	1.12	<5	40	<5	0.95	1	12	94	2460	5.06	<10	0.86	895	83	0.01	3	630	44	<5	<20	43	0.02	<10	12	<10	<1	71
16	G34251	3.4	1.23	<5	50	<5	0.34	1	15	107	2736	5.04	<10	0.80	530	95	0.01	3	610	48	<5	<20	20	0.02	<10	13	<10	<1	132
17	G34252	2.6	1.08	5	40	<5	0.30	<1	12	95	2407	4.85	<10	0.76	413	55	0.01	5	730	30	<5	<20	15	0.02	<10	11	<10	<1	134
18	G34253	2.3	0.25	<5	30	<5	0.52	1	11	186	2511	4.18	<10	0.21	510	23	0.01	6	380	48	<5	<20	31	0.02	<10	4	<10	<1	40
19	G34254	4.0	0.28	80	30	<5	0.20	1	9	183	2675	4.06	<10	0.07	129	46	0.01	5	380	28	10	<20	20	0.01	<10	5	<10	<1	41
20	G34255	3.6	1.11	55	75	<5	0.72	3	15	59	3230	3.77	20	0.52	271	225	0.03	12	350	128	25	<20	30	0.03	<10	43	<10	5	158
21	G34256	2.0	0.26	20	35	<5	0.16	1	10	180	2020	4.72	<10	0.05	65	37	0.01	6	390	36	<5	<20	37	0.01	<10	5	<10	<1	78
22	G34257	1.9	0.35	10	35	<5	0.16	1	9	182	2164	4.65	<10	0.13	116	40	0.01	6	370	24	<5	<20	9	0.01	<10	8	<10	<1	67
23	G34258	1.8	0.65	<5	<5	<5	1.01	<1	11	173	2224	4.40	<10	0.59	757	42	0.01	4	420	30	<5	<20	1372	0.02	<10	10	<10	<1	77
24	G34259	1.5	0.36	20	35	<5	0.24	1	9	211	1515	3.74	<10	0.17	352	78	0.01	6	280	42	<5	<20	13	0.01	<10	4	<10	<1	73
25	G34260	2.1	0.35	<5	30	<5	0.21	<1	10	167	2505	4.09	<10	0.12	123	41	0.02	6	550	36	<5	<20	15	0.01	<10	6	<10	<1	45
26	G34261	3.0	0.25	80	30	<5	0.15	<1	10	157	2357	4.22	<10	0.05	101	42	0.01	6	330	32	<5	<20	12	0.01	<10	5	<10	<1	40
27	G34262	5.8	0.31	235	45	<5	0.19	3	12	171	2037	7.14	<10	0.05	92	19	0.01	4	550	34	<5	<20	10	0.03	<10	5	<10	<1	137
28	G34263	2.5	0.26	115	45	<5	0.22	1	11	145	2330	5.79	<10	<0.01	37	24	0.01	4	640	24	<5	<20	14	0.02	<10	3	<10	<1	16
29	G34264	3.5	0.25	115	50	<5	0.25	2	14	178	2696	7.80	<10	<0.01	47	13	0.01	6	680	32	<5	<20	30	0.03	<10	3	<10	<1	25
30	G34265	9.5	0.21	305	40	<5	0.18	4	13	122	2582	7.04	<10	<0.01	69	11	0.01	4	270	34	40	<20	346	0.02	<10	1	<10	<1	89

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007- 5454 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
31	G34266	3.5	0.21	15	30	<5	0.22	1	12	134	2834	5.64	<10	0.02	101	15	0.01	5	150	24	<5	<20	122	0.02	<10	2	<10	<1	39
32	G34267	2.9	0.25	85	30	<5	0.19	2	9	143	2129	4.08	<10	0.04	80	29	0.01	4	360	38	<5	<20	26	0.01	<10	3	<10	<1	83
33	G34268	3.7	0.27	65	35	<5	0.18	<1	8	153	2130	3.47	<10	0.04	90	48	0.01	4	410	16	<5	<20	20	0.01	<10	4	<10	<1	45
34	G34269	10.3	0.27	110	30	<5	0.21	1	8	151	1877	4.11	<10	0.04	103	37	0.01	4	540	42	<5	<20	20	0.02	<10	5	<10	<1	71
35	G34270	7.4	0.37	60	35	<5	0.21	1	11	147	2572	4.54	<10	0.13	159	34	0.01	5	420	30	<5	<20	15	0.02	<10	5	<10	<1	61
QC DATA:																													
Repeat:																													
1	G34236	11.5	0.29	85	35	<5	0.28	4	10	101	2186	4.35	<10	0.09	179	22	0.01	3	610	166	30	<20	20	0.01	<10	4	<10	<1	178
10	G34245	1.2	1.77	<5	50	<5	2.24	<1	11	65	1856	3.97	<10	1.31	802	54	0.01	3	740	46	<5	<20	286	0.02	<10	20	<10	1	124
19	G34254	3.9	0.28	70	25	<5	0.20	<1	9	182	2718	4.05	<10	0.07	126	47	0.02	6	360	26	5	<20	12	0.01	<10	5	<10	<1	41
Resplit:																													
1	G34236	11.9	0.33	75	35	<5	0.31	4	10	100	2224	4.30	<10	0.12	203	22	0.01	3	610	180	25	<20	25	0.01	<10	5	<10	<1	192
Standard:																													
Pb113		11.4	0.28	70	65	<5	1.72	42	<1	6	2432	0.99	<10	0.10	1519	79	0.02	<1	<10	5528	15	<20	80	0.02	<10	7	10	<1	6913

Aqua Regia Digestion
ICP Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/bp
df/7129
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007- 5455

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

3-Aug-07

No. of samples received: 36
Sample Type: Core
Project: KSM
Shipment #: 07021
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34271	1.36	0.040
2	G34272	0.90	0.026
3	G34273	0.93	0.027
4	G34274	0.72	0.021
5	G34275	1.23	0.036
6	G34276	0.84	0.024
7	G34277	0.92	0.027
8	G34278	0.71	0.021
9	G34279	0.67	0.020
10	G34280	0.63	0.018
11	G34281	0.49	0.014
12	G34282	0.46	0.013
13	G34283	0.45	0.013
14	G34284	0.58	0.017
15	G34285	<0.03	<0.001
16	G34286	0.86	0.025
17	G34287	0.65	0.019
18	G34288	0.57	0.017
19	G34289	0.58	0.017
20	G34290	0.55	0.016
21	G34291	0.60	0.017
22	G34292	0.68	0.020
23	G34293	0.55	0.016
24	G34294	0.56	0.016

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7 - 5455

ET #.	Tag #	Au (g/t)	Au (oz/t)
25	G34295	0.38	0.011
26	G34296	0.48	0.014
27	G34297	0.27	0.008
28	G34298	0.65	0.019
29	G34299	0.40	0.012
30	G34300	0.59	0.017
31	G34301	0.58	0.017
32	G34302	0.61	0.018
33	G34303	0.86	0.025
34	G34304	0.96	0.028
35	G34305	0.90	0.026
36	G36291	0.14	0.004

QC DATA:

Repeat:

1	G34271	1.35	0.039
10	G34280	0.64	0.019
19	G34289	0.58	0.017

Standard:

SI25		1.78	0.052

JJ/jl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5455

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 36
Sample Type: Core
Project: KSM
Shipment #: 07021
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34271	2.8	0.29	<5	35	<5	0.17	2	11	155	2656	4.73	<10	0.07	101	31	0.01	5	140	20	<5	<20	11	0.01	<10	6	<10	<1	53
2	G34272	3.7	0.23	20	40	<5	0.14	2	13	150	2331	4.56	<10	0.04	89	27	0.01	5	70	24	<5	<20	16	0.01	<10	5	<10	<1	36
3	G34273	3.2	0.25	15	45	<5	0.13	2	13	179	2363	4.83	<10	0.05	84	28	0.01	4	60	24	<5	<20	18	0.02	<10	5	<10	<1	36
4	G34274	1.8	0.25	<5	50	<5	0.18	1	10	182	1732	4.84	<10	0.02	91	32	0.02	6	250	20	<5	<20	20	0.02	<10	7	<10	<1	28
5	G34275	1.7	0.27	<5	45	<5	0.15	2	12	156	2841	5.71	<10	0.04	83	19	0.02	5	100	20	<5	<20	15	0.02	<10	5	<10	<1	32
6	G34276	1.5	0.26	<5	45	<5	0.21	2	13	144	1526	5.86	<10	0.01	111	27	0.02	5	350	22	<5	<20	20	0.02	<10	6	<10	<1	33
7	G34277	1.2	0.25	<5	45	<5	0.18	<1	9	141	1446	4.32	<10	0.02	75	27	0.02	4	370	22	<5	<20	10	0.02	<10	5	<10	<1	32
8	G34278	1.5	0.29	<5	45	<5	0.18	2	10	132	1517	5.04	<10	0.05	86	25	0.02	4	380	20	<5	<20	14	0.02	<10	6	<10	<1	47
9	G34279	4.0	0.27	<5	50	<5	0.19	1	13	131	2106	5.22	<10	0.02	64	17	0.02	4	370	18	<5	<20	17	0.02	<10	5	<10	<1	23
10	G34280	3.2	0.30	35	45	<5	0.31	4	12	175	1539	5.36	<10	0.03	122	29	0.02	6	540	60	<5	<20	114	0.02	<10	5	<10	<1	123
11	G34281	2.2	0.26	20	45	<5	0.36	3	12	161	1800	4.88	<10	0.03	178	30	0.01	6	280	54	<5	<20	30	0.02	<10	5	<10	<1	71
12	G34282	1.5	0.29	<5	40	<5	0.28	2	10	161	1762	4.83	<10	0.02	118	14	0.02	5	380	30	<5	<20	27	0.02	<10	5	<10	<1	42
13	G34283	1.4	0.30	<5	45	<5	0.27	2	12	140	2015	4.66	<10	0.03	97	17	0.02	3	440	26	<5	<20	15	0.02	<10	6	<10	<1	56
14	G34284	2.3	0.29	<5	50	<5	0.21	4	12	152	1933	5.79	<10	0.04	88	13	0.01	5	350	50	<5	<20	13	0.02	<10	6	<10	<1	116
15	G34285	<0.2	1.03	<5	275	20	0.61	<1	7	93	9	2.17	<10	0.74	596	2	0.10	5	760	16	<5	<20	103	0.22	<10	52	<10	7	43
16	G34286	3.4	0.33	30	55	<5	0.31	3	13	158	1625	6.58	<10	0.03	91	29	0.02	6	660	52	<5	<20	30	0.03	<10	7	<10	<1	83
17	G34287	2.2	0.29	<5	45	<5	0.33	2	9	189	1803	4.96	<10	0.01	76	39	0.02	5	410	26	<5	<20	51	0.02	<10	6	<10	<1	57
18	G34288	2.6	0.27	25	45	<5	0.30	4	10	181	1402	4.93	<10	0.03	130	32	0.01	5	280	36	5	<20	30	0.02	<10	6	<10	<1	115
19	G34289	2.1	0.22	10	50	<5	0.20	3	9	174	2799	5.12	<10	<0.01	95	35	0.02	5	50	78	<5	<20	16	0.01	<10	4	<10	<1	79
20	G34290	1.8	0.26	10	45	<5	0.23	2	12	185	2299	4.99	<10	0.02	112	29	0.02	5	210	50	<5	<20	30	0.02	<10	5	<10	<1	49
21	G34291	3.2	0.29	<5	40	<5	0.30	6	11	156	1852	5.06	<10	0.03	119	37	0.02	5	330	70	<5	<20	57	0.02	<10	5	<10	<1	314
22	G34292	2.9	0.27	<5	50	<5	0.16	4	12	192	2019	4.20	<10	0.03	64	43	0.02	6	270	84	<5	<20	12	0.02	<10	6	<10	<1	253
23	G34293	1.5	0.27	<5	50	<5	0.13	2	12	160	1746	4.87	<10	0.05	69	32	0.02	5	240	46	<5	<20	9	0.02	<10	5	<10	<1	54
24	G34294	1.7	0.29	15	50	<5	0.17	2	10	178	1502	4.45	<10	0.06	78	21	0.02	5	350	30	<5	<20	9	0.02	<10	5	<10	<1	117
25	G34295	1.6	0.25	<5	45	<5	0.12	2	10	166	2344	4.30	<10	0.03	45	34	0.02	4	190	42	<5	<20	6	0.01	<10	5	<10	<1	79

ECO TECH LABORATORY LTD.

ICP CERTIFICATE OF ANALYSIS AS 2007- 5455

Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34296	1.4	0.26	<5	45	<5	0.14	1	10	161	2066	4.19	<10	0.04	56	25	0.02	5	220	24	<5	<20	8	0.01	<10	5	<10	<1	57
27	G34297	2.9	1.21	10	65	<5	1.06	3	22	63	2619	3.79	30	0.75	208	222	0.04	8	440	62	5	<20	68	0.08	<10	52	<10	8	267
28	G34298	1.8	0.28	<5	45	<5	0.20	2	11	188	2625	5.06	<10	0.03	75	46	0.02	6	220	28	<5	<20	26	0.01	<10	5	<10	<1	55
29	G34299	1.9	0.31	<5	50	<5	0.19	2	10	181	2078	4.57	<10	0.05	62	35	0.02	5	360	24	<5	<20	11	0.01	<10	6	<10	<1	67
30	G34300	2.0	0.36	<5	55	<5	0.17	2	12	181	2032	5.00	<10	0.08	72	29	0.02	5	340	34	<5	<20	12	0.02	<10	6	<10	<1	86
31	G34301	1.8	0.32	<5	55	<5	0.18	3	12	138	2182	4.53	<10	0.07	71	106	0.02	4	320	18	<5	<20	15	0.02	<10	6	<10	<1	139
32	G34302	1.9	0.41	<5	55	<5	0.25	4	11	172	1782	4.38	<10	0.10	98	68	0.02	6	590	32	<5	<20	14	0.02	<10	9	<10	1	294
33	G34303	3.2	0.30	<5	60	<5	0.28	2	15	152	2131	7.35	<10	0.02	111	41	0.02	6	530	38	<5	<20	17	0.03	<10	7	<10	<1	38
34	G34304	4.3	0.31	<5	55	<5	0.26	2	13	170	1841	5.36	<10	0.05	118	46	0.02	7	570	26	<5	<20	19	0.02	<10	10	<10	<1	39
35	G34305	3.8	0.36	15	55	<5	0.21	1	14	150	2206	5.22	<10	0.08	102	117	0.02	5	460	26	<5	<20	20	0.02	<10	8	<10	<1	42
36	G36291	<0.2	1.28	<5	50	<5	1.71	<1	14	99	760	4.06	10	1.13	605	46	0.03	5	1010	24	<5	<20	160	0.05	<10	58	<10	7	45
QC DATA:																													
Repeat:																													
1	G34271	2.7	0.29	<5	40	<5	0.17	2	12	159	2660	4.73	<10	0.07	100	31	0.01	5	160	22	<5	<20	14	0.01	<10	6	<10	<1	52
10	G34280	3.3	0.28	40	40	<5	0.30	4	11	177	1525	5.34	<10	0.03	120	30	0.02	6	540	62	<5	<20	125	0.02	<10	5	<10	<1	124
19	G34289	2.2	0.22	25	45	<5	0.21	3	10	175	2790	5.15	<10	0.01	97	38	0.02	6	60	80	<5	<20	18	0.01	30	4	<10	<1	81
Standard:																													
Pb113		10.9	0.30	45	70	<5	1.78	43	2	6	2408	1.14	<10	0.12	1518	79	0.02	2	70	5536	10	<20	72	0.03	<10	8	10	<1	6983

Aqua Regia Digestion
ICP Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5441
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007- 5456

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

09-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07022
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34306	1.02	0.030
2	G34307	0.66	0.019
3	G34308	0.91	0.027
4	G34309	0.91	0.027
5	G34310	0.83	0.024
6	G34311	<0.03	<0.001
7	G34312	1.11	0.032
8	G34313	0.82	0.024
9	G34314	0.76	0.022
10	G34315	0.99	0.029
11	G34316	0.97	0.028
12	G34317	1.10	0.032
13	G34318	1.02	0.030
14	G34319	1.53	0.045
15	G34320	0.90	<0.001
16	G34321	0.74	0.022
17	G34322	0.81	0.024
18	G34323	0.95	0.028
19	G34324	1.05	0.031
20	G34325	1.08	0.031
21	G34326	0.85	0.025
22	G34327	0.31	0.009
23	G34328	1.03	0.030
24	G34329	0.52	0.015
25	G34330	1.00	0.029
26	G34331	0.90	0.026
27	G34332	1.22	0.036

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 09-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G34333	0.50	0.015
29	G34334	0.78	0.023
30	G34335	1.12	0.033
31	G34336	0.45	0.013
32	G34337	<0.03	<0.001
33	G34338	0.44	0.013
34	G34339	0.53	0.015
35	G34340	0.32	0.009

QC DATA:

Repeat:

1	G34306	1.12	0.033
3	G34308	0.93	0.027
10	G34315	0.94	0.027
14	G34319	1.41	0.041
19	G34324	1.02	0.030
20	G34325	0.99	0.029
30	G34335	1.13	0.033

Resplit:

1	G34306	1.01	0.029

Standard:

SI25		1.78	0.052

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

10-/ 07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5456

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07022
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34306	2.9	0.64	15	25	<5	0.23	<1	13	165	2725	6.96	<10	0.41	298	48	0.02	3	1050	30	<5	<20	15	<0.01	<10	11	<10	2	65
2	G34307	2.4	0.29	50	20	<5	0.26	<1	11	174	2151	4.35	<10	0.10	109	86	0.02	4	1030	26	10	<20	28	<0.01	<10	5	<10	2	47
3	G34308	2.2	0.33	15	20	<5	0.23	<1	13	184	2305	4.84	<10	0.14	91	84	0.02	4	1020	20	<5	<20	21	<0.01	<10	6	<10	2	40
4	G34309	2.0	0.32	25	20	<5	0.27	<1	13	208	2090	5.77	<10	0.09	63	52	0.02	5	1250	22	<5	<20	14	<0.01	<10	8	<10	3	36
5	G34310	3.2	0.26	35	20	<5	0.41	28	12	143	2153	5.12	<10	0.07	81	49	0.02	3	1120	158	10	<20	20	<0.01	<10	6	<10	3	1417
6	G34311	<0.2	4.24	60	145	<5	1.61	<1	29	39	15	8.38	<10	3.30	1395	<1	0.02	<1	1460	24	<5	<20	55	<0.01	<10	163	<10	8	140
7	G34312	2.3	0.78	70	30	<5	0.52	<1	13	165	3666	4.42	<10	0.43	257	155	0.02	4	1010	20	<5	<20	19	<0.01	<10	14	<10	3	38
8	G34313	1.5	0.24	15	20	<5	0.22	<1	10	176	2151	4.69	<10	0.04	44	95	0.02	4	1150	20	<5	<20	12	<0.01	<10	7	<10	2	26
9	G34314	1.4	0.22	20	20	<5	0.17	1	9	152	2013	4.61	<10	0.04	47	76	0.02	3	900	20	<5	<20	11	<0.01	<10	6	<10	2	30
10	G34315	1.5	0.27	20	20	<5	0.21	1	10	173	2159	5.00	<10	0.08	67	75	0.02	4	1110	18	<5	<20	12	<0.01	<10	7	<10	2	41
11	G34316	1.9	0.22	45	25	<5	0.18	<1	12	170	2700	5.25	<10	0.05	42	120	0.02	4	970	20	<5	<20	9	<0.01	<10	7	<10	2	29
12	G34317	2.3	0.27	85	20	<5	0.32	<1	12	170	2486	5.75	<10	0.04	40	76	0.02	4	1610	22	10	<20	13	<0.01	<10	8	<10	3	22
13	G34318	1.9	0.70	20	25	<5	0.21	<1	16	184	2429	6.22	<10	0.44	249	62	0.02	4	1100	20	<5	<20	12	<0.01	<10	14	<10	2	37
14	G34319	1.9	1.39	25	30	<5	0.22	<1	12	177	3114	5.93	<10	0.96	546	65	0.02	4	1130	20	<5	<20	12	<0.01	<10	25	<10	3	59
15	G34320	1.7	0.52	20	20	<5	0.19	<1	13	172	2535	5.02	<10	0.35	165	119	0.02	4	1000	26	<5	<20	11	<0.01	<10	11	<10	2	40
16	G34321	1.3	0.79	20	20	<5	0.26	<1	13	154	2094	5.59	<10	0.58	311	55	0.02	4	1430	20	<5	<20	16	<0.01	<10	16	<10	3	43
17	G34322	1.4	0.67	15	20	<5	0.23	<1	11	157	2141	5.61	<10	0.49	233	35	0.02	4	1200	28	<5	<20	15	<0.01	<10	15	<10	3	33
18	G34323	1.4	0.70	15	20	<5	0.26	<1	12	164	2707	5.16	<10	0.56	220	54	0.02	5	1320	24	<5	<20	16	<0.01	<10	16	<10	3	57
19	G34324	1.1	1.02	15	20	<5	0.29	<1	8	168	1816	3.84	<10	0.88	300	97	0.02	5	1180	16	<5	<20	22	<0.01	<10	20	<10	3	58
20	G34325	1.8	1.01	20	25	<5	0.26	<1	11	129	2432	4.82	<10	0.87	336	97	0.02	4	1180	20	<5	<20	20	<0.01	<10	18	<10	3	42
21	G34327	1.1	1.18	15	120	<5	1.72	<1	12	22	4235	3.47	<10	1.05	726	3	0.15	13	1270	18	<5	<20	174	0.16	<10	149	<10	9	45
22	G34326	3.0	0.70	20	20	<5	0.26	<1	13	164	2612	5.09	<10	0.54	246	43	0.02	4	1280	32	<5	<20	18	<0.01	<10	17	<10	3	47
23	G34328	1.7	0.78	15	20	<5	0.25	<1	10	137	1912	4.59	<10	0.68	294	61	0.02	4	1120	42	<5	<20	16	<0.01	<10	20	<10	3	62
24	G34329	1.2	1.10	15	20	<5	0.35	<1	10	157	1455	3.91	<10	1.01	415	78	0.02	5	1400	20	<5	<20	28	<0.01	<10	26	<10	4	53
25	G34330	2.4	0.87	10	20	<5	0.31	<1	15	166	2573	4.11	<10	0.76	254	120	0.02	6	1300	24	<5	20	31	<0.01	<10	21	<10	3	35

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34331	3.1	0.75	15	20	<5	0.38	<1	10	156	2018	4.19	<10	0.66	312	53	0.02	5	1400	30	<5	<20	26	<0.01	<10	17	<10	3	31
27	G34332	1.4	0.77	15	20	<5	0.73	<1	14	171	1923	4.52	<10	0.79	628	87	0.02	5	1110	28	<5	<20	49	<0.01	<10	18	<10	3	38
28	G34333	1.4	0.94	15	20	<5	0.61	<1	13	107	1580	3.92	<10	0.91	488	66	0.02	4	1420	24	<5	<20	42	<0.01	<10	25	<10	4	43
29	G34334	2.3	0.93	15	20	<5	0.57	<1	16	114	1997	4.46	<10	0.83	409	59	0.02	5	1370	22	<5	<20	36	<0.01	<10	22	<10	4	49
30	G34335	4.7	0.95	20	20	<5	0.57	<1	12	121	2590	4.25	<10	0.91	379	63	0.02	5	1240	20	<5	<20	34	<0.01	<10	23	<10	4	53
31	G34336	17.0	0.42	20	20	<5	1.94	5	9	149	1297	3.32	<10	0.80	1402	57	0.02	5	1130	92	<5	<20	61	<0.01	<10	12	<10	5	141
32	G34337	<0.2	1.03	10	270	<5	0.60	<1	7	97	4	2.28	<10	0.56	571	2	0.09	8	910	10	<5	<20	95	0.15	<10	42	<10	5	48
33	G34338	5.7	0.86	20	25	<5	1.72	<1	11	133	1528	3.80	<10	1.13	1382	49	0.02	5	1420	26	<5	<20	66	<0.01	<10	22	<10	5	52
34	G34339	8.7	0.28	25	20	<5	1.14	1	13	148	1789	5.76	<10	0.32	721	82	0.02	4	1240	122	5	<20	44	<0.01	<10	8	<10	4	22
35	G34340	4.4	0.33	20	15	<5	0.81	<1	17	159	1547	4.58	<10	0.27	486	42	0.02	6	1300	50	<5	<20	40	<0.01	<10	8	<10	3	21
QC DATA:																													
Repeat:																													
1	G34306	2.9	0.63	15	25	<5	0.23	<1	12	166	2704	6.91	<10	0.40	290	55	0.02	3	1040	28	<5	<20	15	<0.01	<10	10	<10	2	65
10	G34315	1.3	0.26	20	20	<5	0.21	<1	9	165	2115	4.94	<10	0.08	61	70	0.02	4	1090	18	<5	<20	11	<0.01	<10	7	<10	2	41
19	G34324	1.1	1.05	15	20	<5	0.30	<1	8	171	1889	3.90	<10	0.89	320	101	0.02	5	1210	16	<5	<20	22	<0.01	<10	20	<10	3	62
Resplit:																													
1	G34306	2.9	0.67	15	20	<5	0.24	<1	13	171	2656	6.88	<10	0.42	304	66	0.02	3	1070	22	<5	<20	16	<0.01	<10	11	<10	2	70
Standard:																													
Pb113		11.4	0.26	60	60	<5	1.79	43	2	1	2376	1.08	<10	0.11	1533	56	0.01	<1	90	5584	<5	<20	79	0.01	<10	6	<10	1	6924

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa/jl
df/n5456S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007-5457

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

3-Aug-07

No. of samples received: 34
Sample Type: Core
Project: KSM
Shipment #: 07023
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36292	0.13	0.004
2	G36293	0.12	0.003
3	G36294	0.15	0.004
4	G36295	0.17	0.005
5	G36296	0.13	0.004
6	G36297	0.19	0.006
7	G36298	0.35	0.010
8	G36299	0.36	0.010
9	G36300	0.27	0.008
10	G36301	<0.03	<0.001
11	G36302	0.19	0.006
12	G36303	0.23	0.007
13	G36304	0.17	0.005
14	G36305	0.25	0.007
15	G36306	0.12	0.003
16	G36307	0.29	0.008
17	G36308	0.26	0.008
18	G36309	0.21	0.006
19	G36310	0.30	0.009
20	G36311	0.30	0.009
21	G36312	0.12	0.003
22	G36313	0.14	0.004
23	G36314	0.21	0.006
24	G36315	0.14	0.004
25	G36316	0.23	0.007
26	G36317	0.12	0.003
27	G36318	0.64	0.019

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 3-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G36319	1.90	0.055
29	G36320	0.26	0.008
30	G36321	0.16	0.005
31	G36322	0.14	0.004
32	G36323	0.20	0.006
33	G36324	0.62	0.018
34	G36325	1.09	0.032

QC DATA:

Repeat:

1	G36292	0.12	0.003
19	G36310	0.36	0.010
33	G36324	0.62	0.018
34	G36325	1.11	0.032

Resplits:

1	G36292	0.11	0.003

Standard:

SI25		1.81	0.053

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

1[illegible]g-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5457

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 34
Sample Type: Core
Project: KSM
Shipment #: 07023
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36292	0.5	0.96	<5	60	<5	2.30	<1	10	70	669	2.88	<10	0.78	655	19	0.02	5	1440	18	5	<20	182	0.03	<10	40	<10	3	47
2	G36293	0.5	1.08	5	45	<5	2.30	1	14	78	887	3.93	<10	0.93	777	13	0.04	5	1320	26	<5	<20	204	0.06	<10	49	<10	3	69
3	G36294	0.6	1.10	15	55	<5	1.93	<1	12	76	814	3.22	<10	0.98	656	96	0.04	4	1490	26	<5	<20	160	0.05	<10	51	<10	5	57
4	G36295	0.8	0.95	<5	35	<5	2.23	<1	12	71	718	3.44	<10	0.75	759	48	0.01	5	1360	20	<5	<20	172	0.04	<10	35	<10	3	49
5	G36296	0.7	1.08	15	70	<5	2.61	<1	10	51	605	3.05	<10	0.85	852	20	0.02	5	1540	22	5	<20	226	0.03	<10	40	<10	5	57
6	G36297	0.7	0.92	10	40	<5	1.45	<1	12	45	610	3.25	<10	0.72	606	28	<0.01	4	1550	26	5	<20	97	0.02	<10	38	<10	3	60
7	G36298	1.3	1.09	50	45	<5	1.20	<1	17	80	1292	3.64	<10	0.85	551	33	0.01	5	1560	24	<5	<20	78	0.02	<10	41	<10	4	55
8	G36299	1.6	0.75	5	40	<5	1.96	<1	12	94	1406	3.16	<10	0.53	590	205	0.01	5	1350	28	<5	<20	145	0.02	<10	27	<10	4	32
9	G36300	0.7	0.86	<5	50	<5	1.81	<1	11	79	858	3.08	<10	0.69	499	91	0.02	4	1430	22	<5	<20	141	0.02	<10	38	<10	5	33
10	G36301	<0.2	1.05	15	235	<5	0.63	<1	5	75	6	2.05	<10	0.57	531	2	0.07	7	840	20	<5	<20	109	0.15	<10	39	<10	5	44
11	G36302	0.7	0.91	<5	55	<5	2.04	1	14	104	1028	3.32	<10	0.69	541	68	0.02	6	1370	26	<5	<20	160	0.03	<10	40	<10	5	37
12	G36303	0.7	1.01	<5	55	<5	2.25	<1	12	98	948	3.91	<10	0.84	530	25	0.04	5	1240	28	<5	<20	192	0.05	<10	51	<10	3	44
13	G36304	0.9	0.92	10	40	<5	3.54	<1	12	71	909	3.76	<10	0.81	876	17	0.03	5	1370	26	<5	<20	330	0.06	<10	46	<10	3	55
14	G36305	0.8	0.97	<5	30	<5	1.74	<1	16	99	1169	4.68	<10	0.77	451	27	0.02	4	1230	34	<5	<20	118	0.06	<10	51	<10	2	38
15	G36306	0.5	1.04	10	55	<5	1.73	<1	10	71	650	3.23	<10	0.89	491	34	0.04	5	1510	28	<5	<20	149	0.07	<10	54	<10	4	47
16	G36307	0.8	1.00	10	45	<5	1.30	<1	15	79	951	4.10	<10	0.82	480	26	0.04	5	1400	34	<5	<20	99	0.08	<10	57	<10	3	60
17	G36308	1.1	1.12	<5	45	<5	2.03	1	18	90	1124	4.98	<10	0.97	666	21	0.06	6	1440	28	<5	<20	165	0.08	<10	77	<10	2	67
18	G36309	0.9	0.93	<5	50	<5	2.84	1	14	73	907	3.94	<10	0.77	841	32	0.05	4	1500	24	<5	<20	240	0.07	<10	72	<10	3	62
19	G36310	1.0	0.93	5	55	<5	2.65	<1	12	84	953	3.78	<10	0.74	841	306	0.05	4	1440	24	<5	<20	207	0.08	<10	74	<10	4	62
20	G36311	1.1	0.87	15	40	<5	2.29	<1	14	79	618	3.79	<10	0.69	780	17	0.04	5	1500	28	<5	<20	188	0.08	<10	51	<10	2	64
21	G36312	0.5	1.06	<5	60	<5	2.41	<1	13	62	721	3.76	<10	0.88	735	20	0.04	4	1610	30	<5	<20	188	0.09	<10	60	<10	4	64
22	G36313	0.7	0.96	<5	50	<5	2.49	2	14	63	703	3.97	<10	0.80	827	41	0.04	7	1600	36	5	<20	220	0.09	<10	54	<10	3	103
23	G36314	1.0	1.04	20	45	<5	1.30	<1	21	101	998	5.37	<10	0.90	517	42	0.05	5	1370	54	<5	<20	120	0.09	<10	65	<10	3	72
24	G36315	0.5	1.02	25	50	<5	2.55	<1	15	62	650	3.82	<10	0.87	784	27	0.05	5	1720	30	5	<20	193	0.08	<10	61	<10	4	69
25	G36316	0.6	1.11	15	50	<5	1.67	<1	15	74	761	4.30	<10	0.94	662	39	0.04	5	1540	30	<5	<20	114	0.09	<10	67	<10	4	67

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36317	0.9	1.04	10	45	<5	1.58	<1	16	52	611	4.14	<10	0.93	619	21	0.04	6	1820	34	<5	<20	103	0.08	<10	61	<10	4	72
27	G36318	1.3	1.04	30	35	<5	2.31	20	16	61	1239	3.87	<10	0.98	846	18	0.03	5	1700	930	<5	<20	207	0.08	<10	52	10	3	696
28	G36319	3.9	1.11	60	50	<5	1.10	<1	23	60	8591	4.18	<10	0.58	209	679	0.05	71	180	72	15	<20	57	0.06	<10	43	<10	3	88
29	G36320	1.1	1.07	20	50	<5	2.03	5	14	95	904	3.93	<10	0.93	840	43	0.04	5	1500	214	<5	<20	184	0.10	<10	49	<10	3	288
30	G36321	0.7	0.98	15	45	<5	2.38	<1	17	73	497	4.61	<10	0.76	804	29	0.05	5	1670	38	<5	<20	143	0.09	<10	73	<10	2	85
31	G36322	0.5	1.03	20	55	<5	2.48	<1	13	57	530	3.64	<10	0.89	869	27	0.06	4	1710	70	<5	<20	154	0.09	<10	79	<10	4	98
32	G36323	1.3	1.03	10	45	<5	1.57	<1	20	61	1273	6.04	<10	0.90	625	25	0.05	5	1490	48	<5	<20	93	0.07	<10	66	<10	2	71
33	G36324	1.2	1.52	20	55	<5	0.70	1	12	97	1148	3.62	<10	1.21	1241	50	<0.01	13	1230	94	10	<20	11	0.03	<10	21	<10	<1	239
34	G36325	3.2	0.52	20	30	<5	0.17	9	13	121	1669	5.46	<10	0.25	251	60	<0.01	18	730	172	<5	<20	1	0.02	<10	7	<10	<1	334
QC DATA:																													
Repeat:																													
1	G36292	0.5	0.94	5	55	<5	2.35	<1	11	69	683	2.93	<10	0.79	667	16	0.02	5	1490	22	<5	<20	187	0.03	<10	40	<10	4	49
19	G36310	1.3	0.92	5	55	<5	2.70	<1	12	84	954	3.88	<10	0.73	853	344	0.05	4	1550	30	<5	<20	201	0.07	<10	73	<10	3	68
Resplit:																													
1	G36292	0.4	0.95	5	60	<5	2.26	<1	10	80	610	3.00	<10	0.79	612	20	0.02	4	1480	30	<5	<20	176	0.03	<10	42	<10	4	51
Standard:																													
Pb113		11.8	0.25	45	60	<5	1.69	40	2	6	2349	1.10	<10	0.09	1491	63	0.02	2	80	5370	15	<20	79	0.02	<10	6	10	<1	7097

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
dl/5457S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007- 5458

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

9-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07025
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36361	0.64	0.019
2	G36362	0.80	0.023
3	G36363	0.88	0.026
4	G36364	0.71	0.021
5	G36365	0.53	0.015
6	G36366	0.97	0.028
7	G36367	0.90	0.026
8	G36368	0.81	0.024
9	G36369	1.07	0.031
10	G36370	1.18	0.034
11	G36371	0.96	0.028
12	G36372	0.82	0.024
13	G36373	1.28	0.037
14	G36374	0.74	0.022
15	G36375	0.64	0.019
16	G36376	0.91	0.027
17	G36377	0.74	0.022
18	G36378	0.99	0.029
19	G36379	0.42	0.012
20	G36380	<0.03	<0.001
21	G36381	0.61	0.018
22	G36382	0.86	0.025
23	G36383	0.97	0.028
24	G36384	0.52	0.015
25	G36385	0.69	0.020
26	G36386	0.62	0.018
27	G36387	0.56	0.016

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 9-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G36388	0.86	0.025
29	G36389	1.05	0.031
30	G36390	0.80	0.023
31	G36391	0.62	0.018
32	G36392	0.80	0.023
33	G36393	0.78	0.023
34	G36394	2.04	0.059
35	G36395	1.19	0.035

QC DATA:

Repeat:

1	G36361	0.71	0.021
6	G36366	0.89	0.026
9	G36369	0.98	0.029
10	G36370	1.18	0.034
13	G36373	1.25	0.036
19	G36379	0.38	0.011
23	G36383	0.98	0.029
34	G36394	1.94	0.057

Resplits:

1	G36361	0.64	0.019

Standard:

SJ32		2.70	0.079

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

8-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5458

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07025
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36361	1.3	0.28	<5	55	<5	0.15	2	9	109	1486	3.91	<10	<0.01	40	39	<0.01	5	540	34	<5	<20	10	0.02	<10	7	<10	<1	150
2	G36362	2.2	0.22	<5	40	<5	0.20	4	9	128	1705	5.07	<10	<0.01	59	23	<0.01	7	770	56	<5	<20	9	0.02	<10	7	<10	<1	338
3	G36363	1.7	0.15	<5	35	<5	0.11	<1	7	151	2111	3.35	<10	<0.01	38	17	<0.01	6	400	28	<5	<20	10	0.01	<10	4	<10	<1	61
4	G36364	1.6	0.20	<5	40	<5	0.15	1	9	196	1820	3.63	<10	<0.01	56	82	0.01	7	570	36	<5	<20	12	0.02	<10	6	<10	<1	42
5	G36365	2.0	0.17	<5	35	<5	0.16	1	8	135	2192	3.91	<10	<0.01	40	21	<0.01	6	610	26	<5	<20	11	0.02	<10	4	<10	<1	29
6	G36366	1.3	0.19	<5	40	<5	0.15	<1	9	145	1825	4.05	<10	<0.01	41	26	<0.01	6	550	26	<5	<20	10	0.02	<10	5	<10	<1	20
7	G36367	1.4	0.20	<5	55	<5	0.16	2	11	142	2018	5.26	<10	<0.01	48	23	<0.01	6	620	30	<5	<20	9	0.02	<10	6	<10	<1	107
8	G36368	1.1	0.21	20	85	<5	0.18	<1	8	172	1763	4.08	<10	<0.01	42	37	0.01	6	680	32	<5	<20	22	0.02	<10	6	<10	<1	14
9	G36369	1.0	0.20	<5	50	<5	0.13	<1	10	132	1735	5.21	<10	<0.01	35	11	<0.01	5	490	26	<5	<20	10	0.02	<10	6	<10	<1	13
10	G36370	1.3	0.30	5	60	<5	0.28	<1	13	153	2230	6.38	<10	<0.01	44	24	<0.01	8	1100	36	<5	<20	11	0.03	<10	10	<10	<1	27
11	G36371	1.2	0.30	<5	65	<5	0.26	2	13	145	1999	5.80	<10	<0.01	43	21	<0.01	8	1030	36	<5	<20	13	0.02	<10	10	<10	<1	26
12	G36372	1.0	0.16	<5	40	<5	0.09	1	10	191	2523	3.14	<10	<0.01	40	21	0.01	8	310	30	<5	<20	11	0.01	<10	5	<10	<1	32
13	G36373	1.3	0.14	<5	35	<5	0.10	<1	11	151	2822	3.93	<10	<0.01	39	22	0.01	6	320	24	<5	<20	12	0.01	<10	5	<10	<1	14
14	G36374	0.8	0.15	5	30	<5	0.11	<1	9	166	2022	4.49	<10	<0.01	32	24	0.01	7	380	32	<5	<20	5	0.02	<10	4	<10	<1	17
15	G36375	1.4	0.14	15	35	<5	0.07	1	9	162	2161	3.82	<10	<0.01	37	74	<0.01	6	170	22	10	<20	10	0.02	<10	4	<10	<1	21
16	G36376	0.9	0.20	<5	50	<5	0.11	1	9	154	1594	4.96	<10	<0.01	47	34	<0.01	7	380	22	<5	<20	9	0.02	<10	6	<10	<1	9
17	G36377	1.2	0.16	45	40	<5	0.11	1	8	162	1496	3.93	<10	<0.01	34	74	<0.01	7	380	24	20	<20	9	0.02	<10	5	<10	<1	26
18	G36378	1.4	0.13	85	30	<5	0.07	1	8	160	1784	3.47	<10	<0.01	31	67	0.01	7	230	26	60	<20	10	0.01	<10	4	<10	<1	48
19	G36379	0.8	0.13	55	45	<5	0.03	<1	6	188	1618	2.43	<10	<0.01	33	52	<0.01	6	50	14	40	<20	8	0.01	<10	3	<10	<1	30
20	G36380	<0.2	1.05	<5	285	10	0.62	<1	6	91	8	2.23	<10	0.55	545	3	0.15	8	860	14	<5	<20	93	0.10	<10	45	<10	2	42
21	G36381	1.0	0.13	55	40	<5	0.04	1	6	184	1427	2.89	<10	<0.01	39	38	0.01	6	100	16	70	<20	6	0.01	<10	3	<10	<1	39
22	G36382	0.7	0.15	45	40	<5	0.07	<1	9	148	1434	4.14	<10	<0.01	35	61	0.01	7	200	30	35	<20	10	0.01	<10	4	<10	<1	22
23	G36383	0.7	0.15	25	35	<5	0.10	<1	9	146	1571	3.47	<10	<0.01	89	68	0.01	6	330	26	25	<20	10	0.01	<10	4	<10	<1	20
24	G36384	0.8	0.14	15	40	<5	0.06	<1	9	155	1227	3.59	<10	<0.01	28	105	0.01	7	180	34	20	<20	8	0.02	<10	4	<10	<1	17
25	G36385	0.6	0.17	5	45	<5	0.08	<1	8	128	1593	3.45	<10	<0.01	32	73	0.01	6	240	26	<5	<20	10	0.01	<10	4	<10	<1	32

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36386	0.7	0.17	<5	40	<5	0.07	<1	8	198	1322	3.26	<10	<0.01	30	93	0.01	6	230	34	5	<20	3	0.01	<10	4	<10	<1	14
27	G36387	1.6	0.13	25	40	<5	0.07	<1	9	171	1244	3.50	<10	<0.01	34	46	0.01	6	220	28	45	<20	10	0.02	<10	4	<10	<1	28
28	G36388	2.3	0.18	20	45	<5	0.13	1	12	148	1644	4.53	<10	<0.01	38	46	0.01	6	440	20	40	<20	16	0.02	<10	5	<10	<1	35
29	G36389	3.7	1.04	55	80	<5	0.71	4	16	59	3351	3.85	10	0.51	268	215	0.04	13	390	130	35	<20	38	0.04	<10	42	<10	5	151
30	G36390	1.4	0.16	<5	40	<5	0.14	1	9	172	1505	3.53	<10	<0.01	37	77	0.01	6	510	18	<5	<20	13	0.01	<10	4	<10	<1	21
31	G36391	1.2	0.14	15	40	<5	0.11	<1	7	177	1184	2.91	<10	<0.01	32	63	0.01	6	400	18	<5	<20	8	0.01	<10	4	<10	<1	27
32	G36392	1.6	0.15	20	50	<5	0.11	1	8	183	1824	3.35	<10	<0.01	33	52	0.01	7	370	24	<5	<20	13	0.01	<10	4	<10	<1	27
33	G36393	1.3	0.14	20	40	<5	0.17	1	9	146	1302	3.49	<10	<0.01	34	71	0.01	6	670	20	<5	<20	11	0.01	<10	5	<10	<1	13
34	G36394	27.7	0.16	135	45	<5	0.10	7	9	186	1387	4.61	<10	<0.01	143	74	0.01	9	280	336	35	<20	14	0.02	<10	4	20	<1	1542
35	G36395	5.8	0.24	15	50	<5	0.05	2	8	223	1449	4.74	<10	<0.01	76	49	0.01	8	130	32	<5	<20	8	0.02	<10	6	<10	<1	292
QC DATA:																													
Repeat:																													
1	G36361	1.4	0.18	<5	40	<5	0.15	2	10	104	1509	3.94	<10	<0.01	41	44	0.01	4	560	36	<5	<20	19	0.02	<10	4	<10	1	151
10	G36370	1.2	0.22	<5	45	<5	0.27	<1	13	148	2237	6.31	<10	<0.01	43	24	0.01	6	1070	34	<5	<20	15	0.03	<10	7	<10	<1	26
19	G36379	0.8	0.11	60	35	<5	0.03	<1	6	185	1646	2.48	<10	<0.01	28	52	0.01	6	50	16	40	<20	11	0.01	<10	3	<10	<1	30
Resplit:																													
1	G36361	1.3	0.24	<5	50	<5	0.15	2	11	113	1526	3.96	<10	<0.01	43	48	0.01	6	580	32	<5	<20	7	0.02	<10	5	<10	<1	140
Standard:																													
pb113		11.8	0.24	45	55	<5	1.74	40	2	5	2385	1.03	<10	0.09	1416	76	0.02	2	70	5496	15	<20	72	0.02	<10	7	10	<1	6995

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
df/5458
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007- 5459

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

8-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07026
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34341	0.67	0.020
2	G34342	0.42	0.012
3	G34343	0.38	0.011
4	G34343	0.78	0.023
5	G34345	0.40	0.012
6	G34346	0.58	0.017
7	G34347	0.78	0.023
8	G34348	0.46	0.013
9	G34349	0.62	0.018
10	G34350	0.95	0.028
11	G34351	0.65	0.019
12	G34352	0.47	0.014
13	G34353	0.48	0.014
14	G34354	<0.03	<0.001
15	G34355	0.50	<0.001
16	G34356	0.45	0.013
17	G34357	0.55	0.016
18	G34358	0.46	0.013
19	G34359	0.60	0.017
20	G34360	0.61	0.018
21	G34361	0.56	0.016
22	G34362	0.63	0.018
23	G34363	0.41	0.012
24	G34364	0.55	0.016
25	G34365	0.40	0.012
26	G34366	0.55	0.016
27	G34367	0.55	0.016

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 08-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G34368	1.18	0.034
29	G34369	1.07	0.031
30	G34370	0.79	0.023
31	G34371	1.11	0.032
32	G34372	0.28	0.008
33	G34373	1.17	0.034
34	G34374	0.69	0.020
35	G34375	0.87	0.025
QC DATA:			
Repeat:			
1	G34341	0.70	0.020
4	G34343	0.73	0.021
7	G34347	0.82	0.024
10	G34350	1.07	0.031
19	G34359	0.58	0.017
29	G34369	0.96	0.028
33	G34373	1.23	0.036
Resplits:			
1	G34341	0.63	0.018
Standard:			
SI25		1.78	0.052

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

09-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5459

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07026
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34341	2.4	0.78	5	20	<5	0.94	<1	19	129	1782	3.95	<10	0.86	631	58	0.02	8	1280	30	<5	<20	32	0.03	<10	22	<10	<1	42
2	G34342	2.9	1.05	10	35	<5	1.48	<1	20	146	1455	4.72	<10	1.28	1018	26	0.02	9	1380	32	<5	<20	45	0.03	<10	34	<10	<1	59
3	G34343	1.0	0.98	20	30	<5	0.70	<1	11	117	932	3.69	<10	0.95	392	100	0.02	7	1550	38	5	<20	28	0.02	<10	28	<10	<1	48
4	G34344	1.3	0.84	10	30	<5	0.47	<1	12	83	1475	3.27	<10	0.80	232	34	0.02	5	1300	26	<5	<20	21	0.02	<10	25	<10	<1	43
5	G34345	1.8	0.82	40	20	<5	0.52	<1	15	137	1163	4.69	<10	0.71	303	37	0.03	8	1330	40	<5	<20	33	0.03	<10	27	<10	<1	51
6	G34346	1.6	1.04	35	30	<5	0.73	<1	14	102	1110	3.99	<10	1.00	561	61	0.02	6	1560	36	<5	<20	37	0.03	<10	31	<10	<1	68
7	G34347	1.9	0.46	10	20	<5	0.59	<1	7	65	1040	2.33	<10	0.50	265	45	0.02	5	940	20	<5	<20	27	0.01	<10	16	<10	<1	46
8	G34348	2.6	0.75	20	25	<5	0.59	1	15	109	2278	3.93	<10	0.70	442	35	0.02	8	1430	34	<5	<20	39	0.02	<10	26	<10	<1	56
9	G34349	1.7	0.95	20	30	<5	0.69	<1	14	122	1225	3.84	<10	0.94	474	135	0.02	8	1530	32	<5	<20	22	0.03	<10	31	<10	<1	60
10	G34350	2.1	0.94	20	25	<5	1.41	<1	13	93	1542	3.62	<10	1.10	771	116	0.02	7	1690	34	5	<20	47	0.02	<10	26	<10	2	57
11	G34351	2.6	1.09	25	30	<5	1.28	<1	16	108	1653	4.48	<10	1.09	694	69	0.03	8	1490	58	<5	<20	39	0.03	<10	29	<10	<1	48
12	G34352	1.0	1.03	15	35	<5	1.88	<1	14	98	1236	3.74	<10	0.97	575	94	0.02	5	1560	38	<5	<20	65	0.03	<10	30	<10	1	59
13	G34353	1.1	1.12	25	45	<5	2.73	<1	19	81	1397	4.37	<10	0.94	831	79	0.02	6	1580	44	<5	<20	91	0.03	<10	29	<10	2	78
14	G34354	<0.2	1.01	20	265	5	0.56	<1	6	66	8	2.14	<10	0.58	581	3	0.10	8	990	16	<5	<20	79	0.15	<10	46	<10	3	46
15	G34355	1.0	1.11	35	45	<5	3.31	<1	15	94	1150	4.14	<10	1.08	1184	52	0.02	6	1550	36	<5	<20	108	0.04	<10	33	10	3	78
16	G34356	1.4	1.04	30	35	<5	2.19	<1	13	106	1187	3.54	<10	1.00	834	68	0.02	7	1600	42	<5	<20	81	0.03	<10	29	<10	2	82
17	G34357	1.6	1.06	45	40	<5	2.47	<1	12	104	1354	3.61	<10	1.06	906	63	0.03	6	1560	42	<5	<20	87	0.03	<10	33	<10	3	68
18	G34358	1.4	1.04	35	45	<5	2.68	<1	12	102	899	3.29	<10	0.86	714	58	0.03	6	1820	38	<5	<20	81	0.03	<10	29	<10	3	66
19	G34359	2.5	0.92	40	30	<5	2.61	<1	16	115	1838	3.76	<10	0.80	825	100	0.03	8	1710	48	<5	<20	80	0.03	<10	31	<10	1	65
20	G34360	2.6	0.86	30	30	<5	2.09	<1	16	119	1783	3.96	<10	0.72	715	71	0.03	7	1550	50	<5	<20	63	0.03	<10	30	<10	1	63
21	G34361	1.8	0.90	20	40	<5	2.80	<1	18	106	1627	5.21	<10	0.79	498	64	0.03	7	1450	46	<5	<20	78	0.03	<10	39	<10	<1	51
22	G34362	1.9	1.13	25	55	<5	2.32	<1	17	108	1350	4.29	<10	0.96	686	41	0.03	7	1550	38	<5	<20	85	0.03	<10	44	<10	2	95
23	G34363	1.3	1.05	40	40	<5	2.39	3	16	91	1123	4.24	<10	0.89	824	207	0.03	7	1700	56	<5	<20	79	0.03	<10	34	<10	2	314
24	G34364	1.3	0.96	30	50	<5	1.64	<1	11	111	1354	3.27	<10	0.79	420	90	0.03	7	1700	38	<5	<20	52	0.02	<10	32	<10	2	68
25	G34365	1.1	1.04	30	50	<5	2.51	<1	15	100	1095	3.75	<10	0.83	718	84	0.03	7	1830	36	<5	<20	101	0.03	<10	31	<10	2	87

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007- 5459 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34366	1.2	1.18	40	55	<5	2.34	<1	15	77	1257	5.14	<10	0.99	675	53	0.03	6	1740	40	<5	<20	119	0.04	<10	46	<10	3	74
27	G34367	1.2	1.10	20	40	<5	2.37	<1	16	94	1323	4.20	<10	0.97	647	115	0.04	6	1610	42	<5	<20	105	0.03	<10	42	<10	3	81
28	G34368	4.0	0.53	45	25	<5	0.23	<1	16	158	2612	4.94	<10	0.18	177	31	<0.01	7	830	38	<5	<20	9	0.03	<10	12	<10	<1	40
29	G34369	2.7	1.25	25	100	<5	0.33	<1	12	147	2014	5.12	<10	0.81	473	33	0.01	8	1150	46	<5	<20	24	0.02	<10	31	10	<1	90
30	G34370	3.3	1.00	35	50	<5	0.20	<1	10	151	2469	4.95	<10	0.54	350	41	<0.01	7	990	42	<5	<20	6	0.02	<10	23	<10	<1	91
31	G34371	4.1	0.47	35	30	<5	0.20	<1	14	172	2624	5.21	<10	0.12	156	25	<0.01	6	990	44	<5	<20	18	0.03	<10	10	<10	<1	62
32	G34372	3.2	1.19	45	50	<5	1.11	2	24	56	2658	3.52	20	0.60	209	210	0.04	11	610	52	10	<20	51	0.06	<10	48	<10	9	280
33	G34373	4.9	0.66	60	25	<5	0.25	<1	13	161	2776	5.64	<10	0.23	274	19	0.01	8	1040	54	<5	<20	7	0.03	<10	13	<10	<1	73
34	G34374	3.0	0.99	25	35	<5	0.23	<1	13	169	2035	5.09	<10	0.40	468	14	<0.01	6	950	38	<5	<20	4	0.03	<10	20	<10	<1	97
35	G34375	2.9	0.84	85	30	<5	0.18	<1	12	182	1713	5.92	<10	0.26	377	17	0.01	7	900	52	<5	<20	6	0.03	<10	19	<10	<1	110
QC DATA:																													
Repeat:																													
1	G34341	2.4	0.82	5	20	<5	0.96	<1	19	132	1812	4.06	<10	0.90	651	58	0.02	8	1290	26	<5	<20	36	0.02	<10	23	<10	<1	42
10	G34350	2.0	0.94	20	30	<5	1.42	<1	13	93	1509	3.65	<10	1.08	768	128	0.03	8	1710	38	<5	<20	48	0.02	<10	26	<10	2	59
19	G34359	2.4	0.88	35	30	<5	2.46	<1	15	109	1797	3.57	<10	0.75	798	98	0.03	6	1670	42	<5	<20	74	0.03	<10	30	<10	1	61
Resplit:																													
1	G34341	2.5	0.82	5	25	<5	1.03	<1	17	127	1753	4.09	<10	0.90	641	61	0.02	7	1310	30	<5	<20	36	0.03	<10	22	<10	<1	48
Standard:																													
Pb113		11.0	0.26	40	60	<5	1.62	40	2	6	2301	1.12	<10	0.09	1503	65	0.02	<1	80	5602	15	<20	80	0.02	<10	7	10	<1	6993

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa/nl
df/5457
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007- 5460

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

8-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07024
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36326	0.56	0.016
2	G36327	0.53	0.015
3	G36328	1.54	0.045
4	G36329	1.21	0.035
5	G36330	0.97	0.028
6	G36331	0.80	0.023
7	G36332	0.56	0.016
8	G36333	0.78	0.023
9	G36334	0.08	0.002
10	G36335	0.63	0.018
11	G36336	0.71	0.021
12	G36337	0.75	0.022
13	G36338	0.87	0.025
14	G36339	1.02	0.030
15	G36340	1.21	0.035
16	G36341	1.20	0.035
17	G36342	1.08	0.031
18	G36343	0.83	0.024
19	G36344	0.71	<0.001
20	G36345	1.16	0.034
21	G36346	0.87	0.025
22	G36347	0.79	0.023
23	G36348	0.99	0.029
24	G36349	0.82	0.024
25	G36350	0.90	0.026
26	G36351	1.06	0.031

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5460 8-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	G36352	1.12	0.033
28	G36353	1.15	0.034
29	G36354	0.93	0.027
30	G36355	0.72	0.021
31	G36356	1.89	0.055
32	G36357	0.83	0.024
33	G36358	<0.03	<0.001
34	G36359	0.62	0.018
35	G36360	0.61	0.018
QC DATA:			
Repeat:			
1	G36326	0.52	0.015
3	G36328	1.38	0.040
4	G36329	1.10	0.032
10	G36335	0.66	0.019
17	G36342	1.21	0.035
19	G36344	0.79	0.023
20	G36345	1.09	0.032
Resplit:			
1	G36326	0.60	0.017
Standard:			
SI25		1.81	0.053

AU: 30g FA/AA-Finish

JJ/jl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5460

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07024
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36326	1.7	0.14	40	15	<5	0.08	<1	7	160	2186	3.34	<10	<0.01	28	9	<0.01	9	380	28	<5	<20	<1	<0.01	<10	3	<10	<1	69
2	G36327	2.1	0.13	50	20	<5	0.05	<1	8	232	2177	3.15	<10	<0.01	29	6	<0.01	9	220	32	<5	<20	4	0.01	<10	3	<10	<1	53
3	G36328	1.7	0.20	25	25	<5	0.19	2	10	198	2642	4.99	<10	<0.01	74	13	<0.01	8	940	42	<5	<20	14	0.02	<10	5	<10	<1	271
4	G36329	1.1	0.18	30	25	<5	0.12	<1	9	222	2089	4.20	<10	<0.01	45	20	<0.01	9	600	28	<5	<20	5	0.01	<10	5	<10	<1	123
5	G36330	1.1	0.19	25	25	<5	0.16	<1	9	125	1899	4.53	<10	<0.01	30	14	0.01	5	790	36	<5	<20	<1	0.02	<10	3	<10	<1	72
6	G36331	0.9	0.24	30	20	<5	0.24	2	10	156	2107	3.73	<10	<0.01	45	19	0.01	6	1240	34	<5	<20	<1	0.01	<10	4	10	<1	390
7	G36332	0.7	0.36	35	45	<5	0.22	<1	6	140	1277	2.16	<10	0.10	113	73	0.01	5	1250	24	<5	<20	<1	<0.01	<10	4	<10	<1	104
8	G36333	0.9	0.26	40	25	<5	0.15	<1	7	185	1700	3.07	<10	0.02	54	34	0.01	6	790	28	<5	<20	<1	<0.01	<10	4	<10	<1	160
9	G36334	0.3	5.00	110	70	20	0.27	<1	55	43	213	>10	<10	3.77	1969	17	<0.01	3	1500	178	<5	<20	<1	0.08	<10	187	<10	<1	601
10	G36335	1.9	0.28	90	30	<5	0.15	2	11	152	1464	5.07	<10	0.04	75	17	<0.01	4	840	76	45	<20	5	0.02	<10	6	<10	<1	207
11	G36336	1.5	0.19	30	25	<5	0.18	1	9	156	1616	4.33	<10	<0.01	52	11	<0.01	6	970	66	<5	<20	3	0.02	<10	4	<10	<1	198
12	G36337	1.1	0.17	35	25	<5	0.15	1	10	181	1574	4.30	<10	<0.01	44	14	<0.01	6	770	104	<5	<20	<1	0.02	<10	3	<10	<1	326
13	G36338	1.1	0.18	10	20	<5	0.14	<1	9	142	1967	4.04	<10	<0.01	34	16	0.01	6	730	30	<5	<20	<1	0.01	<10	3	<10	<1	80
14	G36339	1.2	0.22	35	30	<5	0.15	<1	12	184	1890	6.12	<10	<0.01	44	18	0.01	9	770	36	<5	<20	<1	0.02	<10	3	<10	<1	101
15	G36340	1.0	0.16	25	25	<5	0.09	4	8	137	2180	4.84	<10	<0.01	23	14	0.01	7	410	48	<5	<20	<1	0.01	<10	2	10	<1	851
16	G36341	1.3	0.19	25	25	<5	0.12	1	13	150	2264	6.74	<10	<0.01	31	14	0.01	7	530	58	<5	<20	<1	0.03	<10	3	<10	<1	117
17	G36342	1.2	0.18	45	25	<5	0.18	<1	9	172	2231	4.27	<10	<0.01	49	12	<0.01	5	900	38	<5	<20	<1	0.01	<10	3	<10	<1	30
18	G36343	1.4	0.23	40	30	<5	0.25	<1	11	209	2053	5.68	<10	<0.01	54	14	0.01	8	1280	40	<5	<20	7	0.02	<10	4	<10	<1	27
19	G36344	0.9	0.17	35	20	<5	0.14	<1	11	166	1755	4.97	<10	<0.01	46	14	<0.01	6	720	42	<5	<20	8	0.02	<10	3	<10	<1	16
20	G36345	1.3	0.20	20	15	<5	0.20	1	9	159	2256	4.63	<10	<0.01	110	16	<0.01	8	980	38	<5	<20	3	0.01	<10	4	<10	<1	90
21	G36346	1.0	0.20	10	25	<5	0.15	1	15	171	2119	6.19	<10	<0.01	83	11	0.01	8	730	52	<5	<20	<1	0.02	<10	3	<10	<1	96
22	G36347	1.3	0.22	15	25	<5	0.17	<1	9	185	1792	4.39	<10	<0.01	73	20	0.01	6	880	42	<5	<20	<1	0.02	<10	4	<10	<1	42
23	G36348	1.0	0.39	35	30	<5	0.21	<1	12	149	1658	5.36	<10	0.08	330	15	0.01	7	1090	36	<5	<20	<1	0.02	<10	7	<10	<1	141
24	G36349	1.5	0.19	25	15	<5	0.24	2	8	157	2057	4.74	<10	<0.01	53	18	0.01	6	1220	60	<5	<20	<1	0.02	<10	3	<10	<1	164
25	G36350	1.0	0.15	30	20	<5	0.08	1	9	188	1762	4.53	<10	<0.01	95	29	<0.01	6	370	58	<5	<20	2	0.02	<10	3	<10	<1	85

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36351	1.0	0.18	35	20	<5	0.14	<1	10	184	1909	5.29	<10	<0.01	39	21	<0.01	8	680	32	<5	<20	10	0.02	<10	5	<10	<1	28
27	G36352	0.7	0.19	40	15	<5	0.14	<1	9	183	1699	3.58	<10	<0.01	38	24	<0.01	6	730	34	<5	<20	3	0.01	<10	4	<10	<1	92
28	G36353	1.1	0.37	50	30	<5	0.17	<1	10	182	2252	3.72	<10	0.07	376	41	<0.01	9	890	38	<5	<20	4	0.02	<10	6	<10	<1	82
29	G36354	1.2	0.20	20	30	<5	0.22	<1	10	153	1779	4.63	<10	<0.01	51	31	<0.01	6	1140	32	<5	<20	<1	0.02	<10	4	<10	<1	80
30	G36355	1.1	0.18	30	20	<5	0.19	6	9	177	2184	4.08	<10	<0.01	43	25	<0.01	6	980	30	<5	<20	<1	0.01	<10	4	10	<1	1182
31	G36356	3.9	1.02	45	50	<5	1.08	1	23	61	8586	3.80	10	0.62	201	604	0.05	69	210	68	20	<20	54	0.05	<10	41	10	3	79
32	G36357	0.9	0.16	25	20	<5	0.15	<1	10	173	1628	4.42	<10	<0.01	32	24	<0.01	6	780	32	<5	<20	<1	0.02	<10	3	<10	<1	56
33	G36358	<0.2	0.98	35	255	15	0.60	<1	6	97	7	2.24	<10	0.51	538	3	0.10	6	910	18	<5	<20	68	0.13	<10	43	<10	<1	51
34	G36359	1.1	0.15	25	30	<5	0.11	2	8	188	1623	4.15	<10	<0.01	30	20	<0.01	7	560	30	<5	<20	<1	0.02	<10	3	<10	<1	379
35	G36360	0.8	0.18	30	25	<5	0.17	<1	8	138	1188	3.59	<10	<0.01	35	23	<0.01	4	880	28	<5	<20	<1	0.02	<10	3	<10	<1	71
QC DATA:																													
Repeat:																													
1	G36326	1.8	0.15	30	20	<5	0.08	<1	8	162	2245	3.46	<10	<0.01	30	10	<0.01	9	410	28	<5	<20	<1	0.01	<10	4	<10	<1	72
10	G36335	1.8	0.26	90	20	<5	0.15	3	11	147	1462	5.06	<10	0.03	76	19	<0.01	7	840	76	50	<20	<1	0.02	<10	6	<10	<1	205
19	G36344	1.0	0.18	35	25	<5	0.15	<1	11	164	1807	5.04	<10	<0.01	50	12	0.01	5	710	42	<5	<20	9	0.02	<10	3	<10	<1	16
Resplit:																													
1	G36326	2.0	0.14	35	15	<5	0.09	2	8	175	2289	3.51	<10	<0.01	34	10	<0.01	10	400	30	<5	<20	1	<0.01	<10	5	<10	<1	67
Standard:																													
Pb113		11.2	0.25	45	60	<5	1.66	42	1	6	2226	1.14	<10	0.02	1531	69	0.02	2	90	5552	15	<20	81	0.01	<10	7	10	<1	6981

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa/jl
df/5457
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007- 5464

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

8-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07027
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36396	1.76	0.051
2	G36397	0.95	0.028
3	G36398	0.79	0.023
4	G36399	0.74	0.022
5	G36400	0.94	0.027
6	G36401	0.72	0.021
7	G36402	0.72	0.021
8	G36403	0.77	0.022
9	G36404	0.79	0.023
10	G36405	0.81	0.024
11	G36406	0.81	0.024
12	G36407	1.07	0.031
13	G36408	1.21	0.035
14	G36409	1.34	0.039
15	G36410	0.78	<0.001
16	G36411	1.75	0.051
17	G36412	0.86	0.025
18	G36413	1.58	0.046
19	G36414	1.06	0.031
20	G36415	0.68	0.020
21	G36416	0.62	0.018
22	G36417	1.08	0.031
23	G36418	1.02	0.030
24	G36419	0.81	0.024
25	G36420	0.71	0.021

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5464 8-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	G36421	0.79	0.023
27	G36422	0.75	0.022
28	G36423	1.09	0.032
29	G36424	0.81	0.024
30	G36425	0.66	0.019
31	G36426	<0.03	<0.001
32	G36427	0.66	0.019
33	G36428	1.30	0.038
34	G36429	1.11	0.032
35	G36430	0.67	0.020

QC DATA:

Repeat:

1	G36396	1.74	0.051
2	G36397	0.94	0.027
5	G36400	0.90	0.026
9	G36404	0.84	0.024
10	G36405	0.76	0.022
16	G36411	1.77	0.052
19	G36414	1.01	0.029
33	G36428	1.23	0.036

Resplit:

1	G36396	1.83	0.053

Standard:

SI25		1.78	0.052

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

8-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5464

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07027
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36396	5.7	0.23	40	50	<5	0.05	2	8	238	1729	4.69	<10	<0.01	65	93	0.02	8	60	56	<5	<20	9	0.01	<10	5	<10	<1	161
2	G36397	3.2	0.21	10	35	<5	0.03	1	11	299	2190	4.16	<10	<0.01	52	58	0.01	10	<10	46	<5	<20	3	<0.01	<10	6	<10	<1	86
3	G36398	2.3	0.19	30	50	<5	0.06	2	7	214	1579	3.15	<10	<0.01	85	49	0.01	7	110	30	5	<20	14	<0.01	<10	7	<10	<1	124
4	G36399	1.8	0.23	<5	75	<5	0.08	2	8	220	1491	4.27	<10	<0.01	116	63	0.01	8	200	26	<5	<20	40	0.01	<10	6	<10	<1	65
5	G36400	1.6	0.22	<5	45	<5	0.06	1	10	211	1523	4.08	<10	<0.01	122	81	0.01	7	90	24	<5	<20	16	0.01	<10	6	<10	<1	21
6	G36401	1.4	0.18	5	55	<5	0.03	1	8	236	1476	3.43	<10	<0.01	78	56	0.01	8	<10	20	<5	<20	16	<0.01	<10	5	<10	<1	90
7	G36402	3.1	0.16	<5	45	<5	0.03	2	8	285	1731	3.20	<10	<0.01	96	40	0.01	8	<10	20	<5	<20	16	<0.01	<10	6	<10	<1	292
8	G36403	2.1	0.19	<5	45	<5	0.03	5	10	239	1398	5.14	<10	<0.01	62	67	0.01	9	20	52	<5	<20	19	0.02	<10	6	<10	<1	578
9	G36404	1.8	0.20	<5	50	<5	0.03	2	8	195	1694	3.69	<10	0.01	76	80	0.01	7	<10	46	<5	<20	13	<0.01	<10	6	<10	<1	236
10	G36405	1.9	0.20	25	45	<5	0.05	4	8	189	1382	3.95	<10	0.02	74	64	0.01	8	100	28	<5	<20	12	<0.01	<10	6	<10	<1	505
11	G36406	2.5	0.17	25	30	<5	0.03	2	8	170	1899	3.53	<10	<0.01	65	90	0.01	7	20	18	5	<20	10	0.01	<10	5	<10	<1	173
12	G36407	1.1	0.22	<5	40	<5	0.07	3	9	166	1303	4.28	<10	<0.01	51	64	0.01	6	190	22	<5	<20	10	0.02	<10	5	<10	<1	178
13	G36408	1.3	0.23	5	35	<5	0.08	4	9	157	1643	4.74	<10	<0.01	60	65	0.01	6	200	28	<5	<20	10	0.02	<10	5	<10	<1	332
14	G36409	1.9	0.25	<5	45	<5	0.06	3	10	158	2912	4.14	<10	<0.01	70	108	0.01	5	70	20	<5	<20	8	0.02	<10	6	<10	<1	199
15	G36410	1.5	0.39	10	60	<5	0.16	1	14	200	1643	4.67	<10	0.02	95	92	0.02	8	610	28	<5	<20	11	0.02	<10	8	<10	<1	76
16	G36411	2.1	0.26	10	45	<5	0.18	9	14	164	2841	6.09	<10	<0.01	67	85	0.01	6	590	234	<5	<20	9	0.03	<10	5	<10	<1	818
17	G36412	1.4	0.20	<5	45	<5	0.08	9	8	215	2126	3.47	<10	<0.01	65	103	0.01	7	230	134	<5	<20	1	0.01	<10	6	<10	<1	788
18	G36413	0.2	0.71	2255	80	15	0.71	3	30	26	63	5.03	<10	2.04	807	4	0.16	107	1110	20	10	<20	60	0.11	<10	23	<10	9	64
19	G36414	1.2	0.24	15	40	<5	0.12	3	11	188	3078	5.49	<10	<0.01	76	860	0.02	4	340	70	<5	<20	7	0.02	<10	9	<10	<1	223
20	G36415	1.4	0.24	45	40	<5	0.11	6	7	182	2055	3.36	<10	<0.01	59	179	0.02	7	350	58	15	<20	12	0.01	<10	8	<10	<1	548
21	G36416	1.0	0.18	15	30	<5	0.09	4	8	194	2438	3.64	<10	<0.01	60	90	0.01	6	230	22	<5	<20	4	<0.01	<10	6	<10	<1	441
22	G36417	1.2	0.26	5	40	<5	0.08	2	8	207	2026	4.21	<10	<0.01	52	128	0.02	7	220	24	<5	<20	6	0.02	<10	6	<10	<1	140
23	G36418	1.3	0.21	20	40	<5	0.05	2	9	184	1781	3.28	<10	<0.01	36	169	0.01	6	110	42	<5	<20	9	0.01	<10	6	<10	<1	101
24	G36419	1.0	0.20	15	35	<5	0.04	1	9	233	1329	3.09	<10	<0.01	53	179	0.01	8	70	26	<5	<20	4	0.01	<10	6	<10	<1	133
25	G36420	0.9	0.22	<5	40	<5	0.05	2	8	192	1376	3.12	<10	<0.01	49	128	0.01	5	110	26	<5	<20	14	0.01	<10	5	<10	<1	227

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36421	1.9	0.22	35	75	<5	0.08	4	10	225	1251	3.88	<10	<0.01	108	109	0.01	11	150	32	5	<20	31	0.02	<10	7	<10	<1	273
27	G36422	1.1	0.22	<5	45	<5	0.05	3	11	212	1778	3.84	<10	<0.01	61	246	0.01	12	50	84	<5	<20	10	0.01	<10	7	<10	<1	211
28	G36423	1.1	0.50	15	60	<5	0.12	1	12	206	1414	4.92	<10	0.12	171	134	0.02	17	410	30	<5	<20	15	0.03	<10	12	<10	<1	42
29	G36424	0.9	0.24	<5	45	<5	0.07	4	11	176	1687	4.47	<10	<0.01	92	70	0.01	15	80	194	<5	<20	14	0.02	<10	7	<10	<1	218
30	G36425	1.8	0.26	10	30	<5	0.18	3	11	174	1595	4.42	<10	0.02	95	108	0.01	14	580	132	<5	<20	12	0.02	<10	7	<10	<1	226
31	G36426	<0.2	1.18	10	260	15	0.66	<1	7	117	6	2.23	<10	0.64	562	3	0.13	6	930	22	5	<20	106	0.16	<10	47	<10	2	44
32	G36427	2.4	0.32	<5	40	<5	0.19	1	11	165	2555	5.24	<10	0.01	54	30	0.01	13	690	36	<5	<20	15	0.02	<10	6	<10	<1	43
33	G36428	1.6	1.02	<5	50	<5	0.17	2	13	142	2311	5.30	<10	0.56	416	45	0.01	16	600	30	<5	<20	11	0.03	<10	15	<10	<1	108
34	G36429	1.5	0.31	<5	35	<5	0.15	1	13	198	1980	4.25	<10	0.05	75	92	0.01	14	510	40	<5	<20	15	0.02	<10	6	<10	<1	33
35	G36430	1.5	0.30	<5	40	<5	0.14	1	12	178	1878	3.65	<10	0.05	67	93	0.01	13	420	38	<5	<20	17	0.01	<10	6	<10	<1	50
QC DATA:																													
Repeat:																													
1	G36396	5.8	0.23	40	60	<5	0.05	2	8	240	1691	4.67	<10	<0.01	66	94	0.01	8	70	56	<5	<20	10	0.01	<10	6	<10	<1	162
10	G36405	2.0	0.20	45	30	<5	0.07	6	9	164	1392	4.13	<10	<0.01	71	57	0.01	7	200	32	<5	<20	8	0.01	<10	6	<10	<1	614
19	G36414	1.2	0.24	15	35	<5	0.12	4	11	184	3107	5.64	<10	<0.01	74	882	0.02	4	330	70	<5	<20	6	0.02	<10	9	<10	<1	223
Resplit:																													
1	G36396	6.0	0.20	40	55	<5	0.04	5	8	240	1679	4.65	<10	<0.01	57	81	0.01	9	60	48	<5	<20	11	0.02	<10	5	<10	<1	167
Standard:																													
Pb113		11.6	0.29	55	65	<5	1.71	39	2	5	2415	1.08	<10	0.11	1471	71	0.02	2	80	5446	20	<20	78	0.02	<10	8	10	<1	6948

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
df/5465
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5465

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

3-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07029
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36431	0.42	0.012
2	G36432	0.52	0.015
3	G36433	0.82	0.024
4	G36434	0.49	0.014
5	G36435	0.62	0.018
6	G36436	0.89	0.026
7	G36437	0.70	0.020
8	G36438	0.34	0.010
9	G36439	<0.03	<0.001
10	G36440	0.40	0.012
11	G36441	0.28	0.008
12	G36442	0.33	0.010
13	G36443	0.27	0.008
14	G36444	0.25	0.007
15	G36445	0.60	<0.001
16	G36446	0.49	0.014
17	G36447	0.27	0.008
18	G36448	0.33	0.010
19	G36449	0.29	0.008
20	G36450	0.37	0.011
21	G36451	0.28	0.008
22	G36452	0.99	0.029
23	G36453	0.24	0.007
24	G36454	0.16	0.005
25	G36455	0.29	0.008

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc.AS7 - 5465

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	G36456	0.28	0.008
27	G36457	0.57	0.017
28	G36458	0.57	0.017
29	G36459	0.47	0.014
30	G36460	0.51	0.015
31	G36461	0.16	0.005
32	G36462	0.24	0.007
33	G36463	0.27	0.008
34	G36464	0.49	0.014
35	G36465	0.32	0.009

QC DATA:

Repeat:

1	G36431	0.45	0.013
6	G36436	0.93	0.027
10	G36440	0.44	0.013
15	G36445	0.59	0.017
19	G36449	0.30	0.009
34	G36464	0.53	0.015

Resplit:

1	G36431	0.41	0.012

Standard:

SI25		1.79	0.052

AU: 30g FA/AA-Finish

JJ/jl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

8-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5465

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07029
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36431	1.7	0.30	<5	40	<5	0.15	2	11	165	1900	4.08	<10	0.05	82	55	0.01	12	380	50	<5	<20	24	0.02	<10	6	<10	<1	39
2	G36432	1.8	0.57	<5	35	<5	0.13	1	13	186	2059	4.15	<10	0.29	180	136	0.02	15	410	44	<5	<20	14	0.02	<10	10	<10	<1	55
3	G36433	2.3	0.75	<5	35	<5	0.19	1	17	156	1853	5.52	<10	0.43	274	55	0.01	17	610	62	<5	<20	15	0.03	<10	12	<10	<1	84
4	G36434	2.4	0.34	5	40	<5	0.17	2	13	176	1766	3.96	<10	0.04	64	104	0.01	14	570	102	<5	<20	22	0.02	<10	7	<10	<1	161
5	G36435	1.7	0.42	<5	100	<5	0.18	2	14	181	1873	5.01	<10	0.16	143	51	0.01	13	440	70	<5	<20	43	0.02	<10	9	<10	<1	118
6	G36436	1.5	0.63	<5	55	<5	0.23	1	13	159	1540	4.21	<10	0.37	283	45	0.01	15	510	36	<5	<20	25	0.02	<10	10	<10	<1	88
7	G36437	2.2	0.32	40	70	<5	0.25	3	14	135	1469	4.20	<10	0.04	112	45	0.01	13	840	94	<5	<20	44	0.02	<10	6	<10	<1	220
8	G36438	2.9	0.31	35	80	<5	0.14	2	8	187	1490	2.77	<10	0.06	77	146	0.01	10	480	80	<5	<20	29	0.01	<10	5	<10	<1	121
9	G36439	<0.2	1.01	<5	255	25	0.61	<1	7	98	6	2.19	<10	0.62	543	3	0.13	6	910	10	<5	<20	88	0.14	<10	46	<10	2	41
10	G36440	2.7	0.78	10	180	<5	0.33	2	10	179	1998	3.25	<10	0.06	71	62	0.02	13	1320	54	<5	<20	30	0.02	<10	16	<10	<1	105
11	G36441	2.4	0.32	<5	60	<5	0.15	3	12	181	1561	3.78	<10	0.08	109	45	0.01	12	320	62	<5	<20	29	0.02	<10	6	<10	<1	130
12	G36442	2.5	0.45	<5	165	<5	0.11	2	11	184	1706	3.77	<10	0.09	80	107	0.01	12	200	70	<5	<20	42	0.02	<10	9	<10	<1	117
13	G36443	2.1	0.32	<5	70	<5	0.15	3	11	156	1300	3.76	<10	0.11	92	132	0.01	10	340	128	<5	<20	39	0.02	<10	5	<10	<1	194
14	G36444	0.8	0.48	<5	70	<5	0.15	1	12	174	1258	4.03	<10	0.18	114	61	0.01	12	280	74	<5	<20	22	0.02	<10	8	<10	<1	69
15	G36445	1.2	0.52	<5	65	<5	0.15	1	11	164	1585	3.39	<10	0.25	127	77	0.01	11	250	56	<5	<20	22	0.01	<10	7	<10	<1	48
16	G36446	1.7	0.39	<5	65	<5	0.28	1	11	166	1722	3.32	<10	0.16	131	76	0.01	13	340	52	<5	<20	38	0.01	<10	7	<10	<1	50
17	G36447	1.3	0.75	<5	75	<5	0.64	<1	16	120	1107	4.18	<10	0.35	264	104	0.02	17	2160	30	<5	<20	36	0.03	<10	12	<10	4	57
18	G36448	1.4	0.64	<5	80	<5	0.67	1	15	126	1222	4.25	<10	0.28	333	74	0.01	18	1600	32	<5	<20	33	0.03	<10	10	<10	2	48
19	G36449	1.4	0.58	<5	85	<5	0.26	1	12	165	1098	3.71	<10	0.10	153	61	0.02	13	640	34	<5	<20	17	0.02	<10	7	<10	<1	38
20	G36450	1.7	0.60	<5	85	<5	0.11	<1	12	139	1477	4.21	<10	0.12	59	82	0.02	14	340	46	<5	<20	15	0.02	<10	5	<10	<1	33
21	G36451	1.3	1.00	<5	115	<5	0.26	<1	15	97	1036	4.31	<10	0.42	148	59	0.02	15	1100	48	<5	<20	21	0.02	<10	12	<10	<1	58
22	G36452	3.7	1.20	50	80	<5	0.75	4	17	60	3315	3.93	20	0.55	279	222	0.04	14	400	128	35	<20	35	0.04	<10	46	<10	5	151
23	G36453	1.2	1.27	5	115	<5	0.25	<1	14	112	793	4.07	<10	0.70	239	52	0.02	20	1050	40	<5	<20	24	0.03	<10	20	<10	2	78
24	G36454	1.2	1.48	<5	60	<5	0.29	<1	14	79	747	4.36	<10	1.25	415	26	0.02	24	1260	34	5	<20	11	0.03	<10	21	<10	3	125
25	G36455	1.4	0.86	<5	80	<5	0.20	<1	15	100	898	4.12	<10	0.39	151	49	0.02	21	800	22	<5	<20	18	0.02	<10	14	<10	1	49

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36456	2.2	0.56	<5	40	<5	0.16	1	17	103	686	3.41	<10	0.29	130	60	0.01	20	590	18	<5	<20	15	0.02	<10	8	<10	<1	39
27	G36457	5.6	0.48	<5	70	<5	0.21	1	15	130	1212	3.95	<10	0.11	90	54	0.02	20	760	54	<5	<20	29	0.02	<10	8	<10	<1	40
28	G36458	17.1	0.43	60	45	<5	0.23	4	15	108	995	4.62	<10	0.15	138	111	0.01	17	850	94	30	<20	14	0.02	<10	8	<10	<1	244
29	G36459	12.1	0.48	80	60	<5	0.21	2	14	109	929	3.93	<10	0.06	67	54	0.02	19	840	48	35	<20	17	0.02	<10	8	<10	<1	156
30	G36460	4.1	0.61	30	70	<5	0.22	5	15	111	936	3.88	<10	0.13	64	68	0.02	18	860	38	20	<20	15	0.02	<10	10	<10	<1	314
31	G36461	4.0	0.58	75	60	<5	0.22	1	13	121	491	3.83	<10	0.17	78	113	0.02	18	930	34	25	<20	16	0.02	<10	9	<10	<1	52
32	G36462	6.2	0.82	95	95	<5	0.28	2	13	130	731	3.81	<10	0.18	100	74	0.02	19	1170	56	30	<20	21	0.02	<10	13	<10	3	90
33	G36463	2.1	0.69	15	80	<5	0.31	3	15	119	830	4.16	<10	0.12	81	92	0.02	22	1310	26	5	<20	21	0.02	<10	12	<10	2	156
34	G36464	4.3	1.19	<5	115	<5	0.32	1	12	109	1039	4.79	<10	0.53	226	24	0.02	18	1320	58	<5	<20	16	0.03	<10	20	<10	2	55
35	G36465	2.7	0.98	<5	60	<5	0.23	2	17	133	993	4.68	<10	0.72	322	66	0.02	21	920	52	<5	<20	13	0.03	<10	15	<10	<1	70
QC DATA:																													
Repeat:																													
1	G36431	2.0	0.28	<5	45	<5	0.15	1	11	160	1900	4.08	<10	0.05	83	62	0.01	11	380	50	<5	<20	22	0.02	<10	5	<10	<1	39
10	G36440	2.7	0.76	5	175	<5	0.33	2	10	168	2015	3.27	<10	0.04	70	72	0.02	12	1330	50	<5	<20	27	0.01	<10	9	<10	1	105
19	G36449	1.4	0.52	<5	60	<5	0.26	1	13	158	1116	3.71	<10	0.09	152	63	0.02	13	630	34	<5	<20	20	0.02	<10	5	<10	<1	38
Resplit:																													
1	G36431	1.9	0.31	<5	50	<5	0.14	2	12	155	2054	4.22	<10	0.05	77	59	0.01	12	370	52	<5	<20	21	0.02	<10	7	<10	<1	40
Standard:																													
Pb113		11.0	0.28	50	65	<5	1.71	39	2	6	2341	1.08	<10	0.11	1464	79	0.02	2	80	5413	15	<20	71	0.02	<10	8	10	<1	7065

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
df/5465
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007- 5466

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

3-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07028
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34376	1.07	0.031
2	G34377	1.02	0.030
3	G34378	0.52	0.015
4	G34379	0.95	0.028
5	G34380	0.83	0.024
6	G34381	<0.03	<0.001
7	G34382	1.43	0.042
8	G34383	0.75	0.022
9	G34384	0.92	0.027
10	G34385	1.28	0.037
11	G34386	1.01	0.029
12	G34387	1.49	0.043
13	G34388	1.55	0.045
14	G34389	1.06	0.031
15	G34390	0.97	0.028
16	G34391	0.76	0.022
17	G34392	0.05	0.001
18	G34393	0.99	0.029
19	G34394	<0.03	<0.001
20	G34395	0.18	0.005
21	G34396	0.22	0.006
22	G34397	0.99	0.029
23	G34398	1.12	0.033
24	G34399	0.90	0.026
25	G34400	3.60	0.105
26	G34401	0.65	0.019
27	G34402	11.3	0.330
28	G34403	2.60	0.076

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7 - 5466

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G34404	1.61	0.047
30	G34405	1.48	0.043
31	G34406	0.80	0.023
32	G34407	4.10	0.120
33	G34408	1.02	0.030
34	G34409	1.05	0.031
35	G34410	0.67	0.020

QC DATA:

Repeat:

1	G34376	1.09	0.032
2	G34377	1.05	0.031
10	G34385	1.36	0.040
12	G34387	1.64	0.048
13	G34388	1.44	0.042
19	G34394	<0.03	<0.001
25	G34400	3.54	0.103
27	G34402	10.9	0.318
27	G34402	11.5	0.335
28	G34403	2.68	0.078
32	G34407	4.05	0.118

Standard:

SI25		1.79	0.052

JJ/jl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

8· ·07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5466

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07028
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34376	4.7	0.98	5	45	<5	0.47	3	17	128	2777	5.81	<10	0.48	726	16	0.01	8	790	46	<5	<20	41	0.03	<10	20	<10	<1	92
2	G34377	4.4	0.90	15	65	<5	0.30	1	11	136	2611	4.33	<10	0.39	547	23	0.01	5	560	26	<5	<20	25	0.02	<10	19	<10	<1	53
3	G34378	3.7	0.63	15	45	<5	0.13	1	16	159	2310	4.19	<10	0.23	281	14	0.01	6	370	20	<5	<20	13	0.02	<10	14	<10	<1	44
4	G34379	4.6	0.54	35	40	<5	0.13	1	11	216	2311	4.47	<10	0.14	205	19	0.01	9	480	26	<5	<20	16	0.02	<10	14	<10	<1	31
5	G34380	4.0	0.36	45	35	<5	0.17	1	10	174	1949	4.51	<10	0.04	76	22	0.01	8	690	22	<5	<20	19	0.02	<10	9	<10	<1	16
6	G34381	<0.2	1.11	<5	275	15	0.59	<1	7	93	7	2.11	<10	0.67	572	2	0.11	6	980	18	5	<20	88	0.15	<10	51	<10	3	43
7	G34382	6.1	0.77	35	40	<5	0.14	2	15	182	3330	5.64	<10	0.26	323	24	0.01	8	470	32	<5	<20	16	0.02	<10	17	<10	<1	61
8	G34383	3.9	0.55	10	45	<5	0.09	1	14	200	2529	3.86	<10	0.17	221	17	0.01	7	280	20	<5	<20	23	0.02	<10	12	<10	<1	43
9	G34384	3.8	0.94	20	45	<5	0.17	1	11	134	2284	4.81	<10	0.36	381	19	0.01	6	690	24	<5	<20	26	0.02	<10	19	<10	<1	68
10	G34385	5.0	0.36	45	35	<5	0.15	<1	12	178	2372	4.55	<10	0.08	170	16	0.02	7	460	18	<5	<20	20	0.02	<10	11	<10	<1	25
11	G34386	5.3	0.37	50	45	<5	0.13	2	16	153	2220	5.67	<10	0.06	119	18	0.01	6	460	26	<5	<20	14	0.02	<10	11	<10	<1	35
12	G34387	7.1	0.20	40	40	<5	0.10	2	12	172	3278	4.83	<10	<0.01	32	19	0.01	8	300	38	<5	<20	13	0.02	<10	7	<10	<1	22
13	G34388	6.5	0.21	45	40	<5	0.12	2	22	165	2442	6.86	<10	<0.01	34	16	0.01	7	420	40	<5	<20	22	0.03	<10	6	<10	<1	17
14	G34389	4.7	0.77	10	40	<5	0.18	1	13	216	2665	4.57	<10	0.32	411	13	0.01	9	430	24	<5	<20	24	0.02	<10	17	<10	<1	71
15	G34390	5.9	0.78	15	40	<5	0.13	2	17	170	3216	4.75	<10	0.29	292	16	0.01	8	450	32	<5	<20	17	0.02	<10	18	<10	<1	59
16	G34391	4.5	0.78	25	35	<5	0.17	1	14	169	2277	4.95	<10	0.29	312	17	0.01	7	670	32	<5	<20	11	0.02	<10	16	<10	<1	42
17	G34392	0.5	3.58	10	125	15	0.35	1	31	45	43	7.44	<10	2.99	1046	5	0.01	4	1350	54	5	<20	39	0.06	<10	109	<10	7	135
18	G34393	3.8	1.14	50	70	<5	0.76	3	17	59	3399	3.86	20	0.57	285	220	0.04	13	340	128	25	<20	38	0.04	<10	47	<10	5	153
19	G34394	0.7	3.81	5	125	20	0.49	1	28	33	149	8.04	<10	3.23	1058	8	0.01	6	1500	52	10	<20	54	0.06	<10	116	<10	5	123
20	G34395	1.6	2.64	20	60	<5	0.49	<1	36	37	75	7.44	<10	2.08	817	5	0.01	3	1490	52	<5	<20	55	0.05	<10	77	<10	5	107
21	G34396	1.9	2.24	70	45	25	0.32	3	36	35	93	8.49	<10	1.58	759	6	<0.01	6	1380	60	5	<20	36	0.06	<10	55	<10	3	151
22	G34397	7.3	0.33	55	40	<5	0.13	3	27	159	3354	5.76	<10	0.03	70	19	0.01	7	430	60	<5	<20	17	0.02	<10	12	<10	<1	19
23	G34398	5.5	1.04	10	45	<5	0.14	2	15	187	3261	5.26	<10	0.41	383	24	0.01	8	470	26	<5	<20	12	0.02	<10	24	<10	<1	49
24	G34399	4.1	1.38	10	55	<5	0.16	2	18	172	2729	5.36	<10	0.57	467	23	0.01	8	590	34	<5	<20	12	0.03	<10	32	<10	<1	62
25	G34400	6.9	0.57	45	30	<5	0.14	2	15	195	3021	5.03	<10	0.15	178	30	0.01	8	470	34	<5	<20	12	0.02	<10	15	<10	<1	25

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34401	3.7	1.55	20	55	<5	0.16	2	27	173	2439	5.92	<10	0.55	612	21	0.01	10	630	36	<5	<20	14	0.03	<10	40	<10	<1	73
27	G34402	8.3	0.48	<5	50	<5	0.11	2	17	155	2013	>10	<10	0.06	162	10	0.01	8	340	40	<5	<20	14	0.05	<10	16	<10	<1	24
28	G34403	5.9	0.28	20	35	<5	0.09	1	11	179	3914	4.65	<10	0.03	84	13	0.01	7	230	34	<5	<20	15	0.01	<10	10	<10	<1	14
29	G34404	6.4	0.33	10	30	<5	0.10	1	13	164	4180	4.98	<10	0.05	112	16	0.01	7	230	34	<5	<20	13	0.01	<10	10	<10	<1	18
30	G34405	5.8	0.55	10	35	<5	0.18	2	11	155	4182	4.66	<10	0.16	224	21	0.01	7	420	20	<5	<20	20	0.01	<10	15	<10	<1	32
31	G34406	4.2	0.36	5	40	<5	0.10	1	11	199	2719	5.34	<10	0.07	138	27	0.01	8	210	32	<5	<20	15	0.02	<10	17	<10	<1	23
32	G34407	5.9	0.49	55	60	<5	0.17	1	15	159	3149	6.75	<10	0.09	136	15	0.01	7	580	38	<5	<20	22	0.03	<10	15	<10	<1	26
33	G34408	6.2	0.78	20	35	<5	0.22	1	13	177	4247	4.73	<10	0.32	367	19	0.02	8	360	22	<5	<20	26	0.02	<10	21	<10	<1	48
34	G34409	4.5	0.44	20	30	<5	0.14	2	17	169	3556	4.94	<10	0.10	158	19	0.01	7	460	26	<5	<20	13	0.01	<10	13	<10	<1	32
35	G34410	2.4	1.09	10	40	<5	0.18	2	12	164	1943	6.06	<10	0.45	462	24	0.01	9	680	26	<5	<20	21	0.03	<10	28	<10	<1	80
QC DATA:																													
Repeat:																													
1	G34376	4.6	1.00	<5	40	<5	0.47	4	17	133	2776	5.78	<10	0.48	722	15	0.01	7	770	44	<5	<20	40	0.03	<10	20	<10	<1	89
10	G34385	4.8	0.37	40	35	<5	0.15	1	12	181	2389	4.51	<10	0.08	168	17	0.02	8	460	18	<5	<20	20	0.02	<10	12	<10	<1	25
19	G34394	0.6	4.02	10	130	10	0.50	2	29	35	156	8.29	<10	3.42	1094	7	0.01	5	1530	54	15	<20	59	0.06	<10	121	<10	6	124
Resplit:																													
1	G34376	4.3	0.97	<5	35	<5	0.44	5	15	118	2796	5.92	<10	0.54	710	17	0.01	6	770	42	<5	<20	43	0.03	<10	22	<10	<1	106
Standard:																													
Pb113		11.0	0.31	55	65	<5	1.78	42	2	5	2326	1.12	<10	0.13	1527	63	0.02	2	80	5570	15	<20	80	0.01	<10	9	40	<1	6988

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa/jl
dl/5465
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5467

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

08-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07030
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36466	0.40	0.012
2	G36467	0.87	0.025
3	G36468	0.25	0.007
4	G36469	0.47	0.014
5	G36470	0.50	0.015
6	G36471	0.34	0.010
7	G36472	0.24	0.007
8	G36473	0.33	0.010
9	G36474	0.35	0.010
10	G36475	0.39	0.011
11	G36476	0.24	0.007
12	G36477	0.23	0.007
13	G36478	0.28	0.008
14	G36479	0.24	0.007
15	G36480	0.43	0.013
16	G36481	0.31	0.009
17	G36482	0.27	0.008
18	G36483	<0.03	<0.001
19	G36484	0.80	0.023
20	G36485	0.74	0.022
21	G36486	0.30	0.009
22	G36487	0.23	0.007
23	G36488	0.43	0.013
24	G36489	0.31	0.009
25	G36490	0.15	0.004

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5467 08-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	G36491	0.17	0.005
27	G36492	0.21	0.006
28	G36493	0.29	0.008
29	G36494	0.12	0.003
30	G36495	0.34	0.010
31	G36496	0.18	0.005
32	G36497	0.17	0.005
33	G36498	0.28	0.008
34	G36499	0.23	0.007
35	G36500	0.32	0.009
QC DATA:			
Repeat:			
1	G36466	0.40	0.012
4	G36469	0.43	0.013
10	G36475	0.38	0.011
15	G36480	0.43	0.013
19	G36484	0.78	0.023
Resplit:			
1	G36466	0.42	0.012
Standard:			
SI25		1.78	0.052

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5467

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07030
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36466	7.4	0.39	55	35	<5	0.19	4	15	107	960	4.07	<10	0.21	144	97	0.01	19	910	66	25	<20	7	0.01	10	7	<10	<1	202
2	G36467	6.4	0.69	10	35	<5	0.24	3	20	112	1035	5.19	<10	0.49	298	48	0.01	23	1160	124	<5	<20	9	0.02	<10	13	<10	<1	163
3	G36468	3.2	0.93	5	40	<5	0.30	2	18	115	881	4.77	<10	0.72	402	67	0.01	22	1500	44	<5	<20	14	0.02	<10	20	<10	<1	131
4	G36469	2.3	1.22	20	45	<5	0.24	1	19	148	805	5.02	<10	1.05	548	100	0.01	26	1190	40	10	<20	9	0.02	<10	25	<10	<1	127
5	G36470	6.1	0.40	10	40	<5	0.32	3	13	113	699	4.76	<10	0.14	113	150	0.01	30	1570	38	<5	<20	9	0.02	<10	8	<10	1	86
6	G36471	6.9	0.42	15	30	<5	0.46	2	10	139	375	3.57	<10	0.15	110	108	0.01	25	2390	112	<5	<20	8	0.02	<10	8	<10	2	82
7	G36472	2.7	1.65	10	35	<5	0.36	2	22	129	1151	6.00	<10	1.55	965	35	0.01	25	1010	66	10	<20	14	0.03	<10	41	<10	<1	134
8	G36473	1.3	0.94	<5	45	<5	1.21	1	20	117	1115	4.87	<10	0.90	724	42	0.01	21	720	58	5	<20	39	0.03	<10	22	<10	<1	52
9	G36474	0.8	0.86	<5	40	<5	1.92	2	14	136	949	4.16	<10	0.81	542	56	0.02	16	620	42	5	<20	59	0.02	<10	22	<10	<1	47
10	G36475	0.8	0.84	5	35	<5	2.75	2	13	132	944	3.80	<10	0.81	745	53	0.02	21	630	56	15	<20	81	0.02	<10	19	<10	<1	53
11	G36476	0.8	0.85	<5	35	<5	1.55	2	14	141	890	4.83	<10	0.79	547	39	0.01	17	710	46	10	<20	47	0.02	<10	20	<10	<1	65
12	G36477	0.6	0.86	<5	40	<5	1.84	<1	11	181	763	3.64	<10	0.81	578	67	0.02	15	660	36	<5	<20	53	0.02	<10	20	<10	<1	50
13	G36478	0.8	0.64	5	35	<5	1.75	1	16	158	878	4.63	<10	0.54	627	42	0.01	16	910	62	<5	<20	58	0.03	<10	15	<10	<1	68
14	G36479	1.3	0.91	25	35	<5	0.96	4	20	118	1270	5.13	<10	0.89	487	43	0.01	24	960	78	25	<20	31	0.02	<10	16	<10	<1	138
15	G36480	1.2	0.38	<5	25	<5	2.16	2	14	131	1106	4.17	<10	0.23	602	93	0.01	16	720	64	10	<20	68	0.02	<10	6	<10	<1	38
16	G36481	0.9	1.53	<5	40	<5	3.31	4	15	107	695	4.08	<10	1.66	1123	47	0.01	20	1110	74	5	<20	105	0.03	<10	30	<10	3	162
17	G36482	0.6	2.57	20	45	<5	2.45	2	19	82	848	4.88	<10	3.38	1502	114	0.01	32	1280	86	25	<20	60	0.06	<10	63	<10	3	167
18	G36483	<0.2	1.07	20	280	20	0.64	<1	8	98	5	2.08	<10	0.61	537	4	0.11	8	830	14	<5	<20	79	0.14	<10	49	<10	3	48
19	G36484	2.1	2.49	240	60	<5	7.95	14	33	68	1175	>10	<10	3.43	6105	38	0.01	32	5520	230	160	<20	147	0.11	<10	78	10	2	1025
20	G36485	0.8	1.31	45	40	<5	2.21	2	14	121	435	3.66	<10	1.52	1450	114	0.01	21	1200	58	45	<20	51	0.03	<10	25	<10	<1	115
21	G36486	0.4	1.60	30	50	<5	4.40	<1	10	113	488	2.73	<10	1.87	1937	149	<0.01	22	1140	44	25	<20	79	0.03	<10	26	<10	2	69
22	G36487	0.5	1.75	25	55	<5	4.92	<1	12	85	455	3.81	<10	1.94	1811	106	0.01	16	1440	42	<5	<20	93	0.05	<10	28	<10	1	87
23	G36488	1.0	2.74	20	65	<5	6.29	2	27	72	1991	7.24	<10	3.20	3609	164	0.01	37	2560	56	30	<20	147	0.07	<10	72	<10	3	238
24	G36489	3.1	1.23	40	55	<5	1.12	3	21	60	2674	3.61	20	0.63	222	203	0.04	12	340	60	10	<20	51	0.05	<10	49	<10	6	275
25	G36490	3.2	1.56	80	45	<5	2.55	2	12	82	597	3.20	<10	1.91	1701	87	<0.01	22	1490	66	115	<20	54	0.04	<10	32	<10	3	112

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36491	0.8	1.65	30	45	<5	0.55	1	16	107	614	4.02	<10	1.88	826	207	<0.01	27	1090	54	25	<20	17	0.02	<10	50	<10	<1	89
27	G36492	1.3	0.75	35	40	<5	0.56	<1	11	111	827	3.04	<10	0.66	445	156	<0.01	15	860	36	20	<20	17	0.02	<10	12	<10	<1	53
28	G36493	1.6	0.73	30	35	<5	0.47	<1	10	130	943	2.67	<10	0.63	338	175	0.01	20	930	38	35	<20	15	0.01	<10	16	<10	<1	53
29	G36494	1.4	0.99	10	45	<5	2.25	1	16	132	723	3.54	<10	0.99	986	111	0.01	20	760	48	10	<20	56	0.03	<10	24	<10	1	59
30	G36495	1.2	1.12	<5	45	<5	2.10	2	21	112	1183	5.09	<10	1.03	723	86	0.01	21	710	42	10	<20	56	0.03	<10	26	<10	<1	82
31	G36496	0.8	0.80	<5	45	<5	1.79	1	16	108	817	4.29	<10	0.67	517	65	0.01	19	850	52	<5	<20	51	0.02	<10	17	<10	1	69
32	G36497	0.7	0.84	<5	45	<5	1.91	2	16	116	836	3.85	<10	0.76	479	93	0.02	19	720	56	15	<20	60	0.02	<10	24	<10	1	88
33	G36498	0.9	1.14	<5	45	<5	2.02	2	24	104	1133	5.11	<10	1.00	463	101	0.03	25	1040	40	10	<20	69	0.02	<10	31	<10	1	83
34	G36499	0.5	1.02	<5	40	<5	3.83	5	17	90	545	3.52	<10	0.99	721	121	0.02	40	1940	102	10	<20	133	0.02	<10	43	<10	4	142
35	G36500	0.5	1.15	5	35	<5	3.64	2	25	112	679	4.04	<10	1.18	689	172	0.02	52	1380	52	10	<20	119	0.03	<10	74	<10	4	69
QC DATA:																													
Repeat:																													
1	G36466	7.1	0.40	45	40	<5	0.20	4	15	106	998	4.07	<10	0.21	139	100	0.01	18	910	64	25	<20	10	0.02	<10	6	<10	<1	200
10	G36475	0.8	0.83	<5	45	<5	2.78	<1	13	131	935	3.84	<10	0.79	750	51	0.02	20	620	56	<5	<20	82	0.03	<10	18	<10	<1	54
19	G36484	1.9	2.33	235	35	<5	7.95	11	30	63	1173	>10	<10	3.28	6011	34	<0.01	29	5450	218	150	<20	139	0.10	<10	74	<10	<1	1033
Resplit:																													
1	G36466	6.9	0.37	50	35	<5	0.17	3	15	110	973	4.08	<10	0.19	139	101	0.01	20	890	66	20	<20	7	0.02	<10	6	<10	<1	198
Standard:																													
Pb113		11.6	0.26	60	55	<5	1.68	41	2	5	2278	1.12	<10	0.10	1498	66	0.02	3	80	5576	15	<20	82	<0.01	<10	8	10	<1	7087

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
df/7175
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007- 5468

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

3-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07031
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34411	0.84	0.024
2	G34412	0.67	0.020
3	G34413	1.43	0.042
4	G34414	1.09	0.032
5	G34415	0.27	0.008
6	G34416	0.61	0.018
7	G34417	0.78	0.023
8	G34418	0.96	0.028
9	G34419	0.76	0.022
10	G34420	1.10	0.032
11	G34421	0.92	0.027
12	G34422	0.82	0.024
13	G34423	0.80	0.023
14	G34424	0.86	0.025
15	G34425	0.92	0.027
16	G34426	1.14	0.033
17	G34427	0.65	0.019
18	G34428	0.78	0.023
19	G34429	1.16	0.034
20	G34430	0.93	0.027
21	G34431	1.61	0.047
22	G34432	1.49	0.043
23	G34433	0.60	0.017
24	G34434	<0.03	<0.001
25	G34435	0.75	0.022
26	G34436	0.87	0.025
27	G34437	1.35	0.039

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 3-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G34438	1.24	0.036
29	G34439	0.88	0.026
30	G34440	0.76	0.022
31	G34441	1.46	0.043
32	G34442	1.22	0.036
33	G34443	0.93	0.027
34	G34444	0.48	0.014
35	G34445	1.36	0.040

QC DATA:

Repeat:

1	G34411	0.83	0.024
3	G34413	1.35	0.039
8	G34418	0.86	0.025
10	G34420	1.13	0.033
19	G34429	1.12	0.033
22	G34432	1.52	0.044
31	G34441	1.54	0.045

Resplits:

1	G34411	0.95	0.028

Standard:

SI25		1.81	0.053

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

20-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5468

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07031
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34411	4.2	0.41	<5	35	<5	0.13	2	21	170	3449	5.43	<10	0.10	179	25	0.01	8	340	34	<5	<20	18	0.01	<10	13	<10	<1	51
2	G34412	3.1	0.91	<5	45	<5	0.28	2	18	131	3142	6.11	<10	0.36	498	21	0.01	6	520	26	<5	<20	35	0.03	<10	27	<10	<1	59
3	G34413	4.2	0.25	40	45	<5	0.17	2	15	172	3121	6.48	<10	<0.01	64	23	0.01	9	560	36	<5	<20	21	0.02	<10	9	<10	<1	22
4	G34414	3.6	0.71	15	45	<5	0.11	2	15	157	3295	5.60	<10	0.22	325	19	0.01	9	280	34	<5	<20	17	0.02	<10	22	<10	<1	50
5	G34415	3.2	1.18	35	50	<5	1.11	3	25	58	2629	3.59	20	0.63	215	203	0.04	11	460	60	15	<20	69	0.05	<10	49	<10	7	280
6	G34416	2.5	1.14	10	65	<5	0.16	1	12	194	2389	5.08	<10	0.43	561	32	0.01	9	580	34	<5	<20	21	0.03	<10	29	<10	<1	104
7	G34417	3.2	0.64	5	40	<5	0.14	1	17	160	2881	4.98	<10	0.19	287	29	0.01	7	430	26	<5	<20	17	0.02	<10	19	<10	<1	54
8	G34418	3.7	0.61	15	40	<5	0.12	2	23	173	2811	5.32	<10	0.20	287	22	0.01	10	300	42	<5	<20	20	0.02	<10	20	<10	<1	61
9	G34419	3.2	0.78	10	45	<5	0.13	1	15	152	3092	5.26	<10	0.24	347	17	0.01	6	370	32	<5	<20	22	0.02	<10	24	<10	<1	55
10	G34420	3.9	0.39	35	40	<5	0.11	2	14	207	3732	5.65	<10	0.07	160	31	0.01	9	300	48	<5	<20	16	0.01	<10	15	<10	<1	33
11	G34421	3.6	0.35	90	40	<5	0.16	3	11	138	2279	6.16	<10	0.07	136	26	0.01	10	560	34	10	<20	17	0.01	<10	11	<10	<1	33
12	G34422	3.5	0.57	20	40	<5	0.12	1	10	173	2741	4.95	<10	0.19	235	16	0.01	8	340	28	<5	<20	15	0.02	<10	17	<10	<1	41
13	G34423	3.2	1.15	<5	50	<5	0.15	2	12	138	2617	6.01	<10	0.46	493	20	0.01	7	510	34	<5	<20	20	0.03	<10	33	<10	<1	85
14	G34424	4.1	1.07	20	45	<5	0.17	2	14	168	3134	6.20	<10	0.41	458	18	0.01	11	480	50	<5	<20	22	0.02	<10	31	<10	<1	66
15	G34425	4.8	0.23	30	40	<5	0.15	2	11	146	2560	5.54	<10	<0.01	79	21	0.01	8	510	34	<5	<20	19	0.02	<10	9	<10	<1	52
16	G34426	5.7	0.28	40	40	<5	0.14	2	14	179	3306	6.38	<10	0.01	101	23	0.01	9	420	36	<5	<20	20	0.02	<10	11	<10	<1	46
17	G34427	2.7	0.74	20	45	<5	0.16	2	11	172	2048	4.93	<10	0.26	356	17	0.01	7	590	34	<5	<20	21	0.02	<10	21	<10	<1	59
18	G34428	3.9	0.59	35	40	<5	0.16	2	12	155	2580	5.90	<10	0.18	272	23	0.01	10	550	42	<5	<20	17	0.03	<10	18	<10	<1	62
19	G34429	3.2	0.27	30	35	<5	0.13	<1	9	165	2735	4.56	<10	0.04	104	15	0.01	7	310	36	<5	<20	19	0.01	<10	10	<10	<1	23
20	G34430	2.5	1.31	15	50	<5	0.25	2	11	143	2581	6.88	<10	0.63	483	20	0.01	10	580	42	10	<20	24	0.03	<10	42	<10	<1	79
21	G34431	3.1	0.48	25	40	<5	0.20	2	10	134	2967	5.06	<10	0.16	242	20	0.01	7	420	30	<5	<20	21	0.02	<10	16	<10	<1	38
22	G34432	2.8	0.72	40	45	<5	0.51	3	9	155	2818	4.99	<10	0.37	581	18	0.01	10	310	30	10	<20	47	<0.01	<10	22	<10	<1	54
23	G34433	1.8	0.98	20	50	<5	1.26	1	12	68	1663	4.62	<10	0.61	1211	18	<0.01	6	910	44	<5	<20	80	0.05	<10	11	<10	3	56
24	G34434	<0.2	0.99	<5	255	15	0.52	<1	8	94	9	2.18	<10	0.59	533	1	0.09	6	950	24	<5	<20	91	0.13	<10	47	<10	3	46
25	G34435	2.5	0.74	20	50	<5	0.71	3	13	100	1866	4.72	<10	0.50	752	20	<0.01	6	840	46	<5	<20	34	0.03	<10	11	<10	2	91

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34436	3.3	0.59	25	45	<5	0.40	2	8	124	2866	4.65	<10	0.41	437	21	0.01	7	440	48	<5	<20	24	0.02	<10	10	<10	<1	47
27	G34437	3.8	0.75	15	55	<5	0.16	<1	11	161	4237	4.36	<10	0.38	261	19	0.01	8	240	36	<5	<20	16	0.01	<10	12	<10	<1	45
28	G34438	3.1	0.69	65	40	<5	0.51	2	12	104	2587	4.97	<10	0.38	419	15	<0.01	5	690	40	<5	<20	37	0.02	<10	9	<10	2	57
29	G34439	3.4	0.70	30	40	<5	0.37	2	12	148	2868	5.01	<10	0.41	399	20	<0.01	8	540	42	<5	<20	27	0.02	<10	11	<10	<1	56
30	G34440	4.0	0.40	60	45	<5	0.23	2	10	124	2204	4.72	<10	0.15	165	23	<0.01	6	700	46	<5	<20	18	0.02	<10	7	<10	<1	63
31	G34441	4.3	0.70	20	45	<5	0.30	2	16	150	3596	4.97	<10	0.31	298	18	<0.01	8	640	30	<5	<20	22	0.01	<10	12	<10	1	64
32	G34442	2.2	1.02	55	50	<5	0.36	2	11	96	1930	4.61	<10	0.55	448	42	<0.01	5	970	32	<5	<20	20	0.02	<10	12	<10	2	77
33	G34443	2.3	0.89	45	45	<5	0.45	3	12	89	1981	4.94	<10	0.46	467	27	<0.01	9	960	30	15	<20	29	0.02	<10	12	<10	2	82
34	G34444	2.4	0.89	20	45	<5	1.91	1	10	61	1470	4.43	<10	0.44	1113	16	<0.01	4	980	28	<5	<20	144	0.04	<10	10	<10	2	73
35	G34445	4.6	0.90	5	35	<5	2.89	1	21	103	3603	4.52	<10	0.57	1219	28	0.01	5	770	30	<5	<20	300	0.03	<10	18	<10	3	53
QC DATA:																													
Repeat:																													
1	G34411	3.8	0.39	<5	40	<5	0.12	1	20	163	3252	5.14	<10	0.08	168	27	0.01	6	320	26	<5	<20	19	0.02	<10	12	<10	<1	38
10	G34420	3.7	0.40	45	40	<5	0.12	2	14	215	3786	5.70	<10	0.07	163	31	31.00	10	290	50	<5	<20	16	0.02	<10	16	<10	<1	33
19	G34429	<0.2	0.28	30	30	<5	0.13	1	10	173	2862	4.79	<10	0.05	111	15	0.01	7	340	38	<5	<20	19	0.02	<10	10	<10	<1	24
Resplit:																													
1	G34411	4.4	0.37	<5	35	<5	0.13	3	21	169	3709	5.52	<10	0.08	172	28	0.01	10	320	30	<5	<20	19	<0.01	<10	12	<10	<1	35
Standard:																													
Pb113		11.8	0.26	40	55	<5	1.68	40	3	6	2306	1.19	<10	0.10	1570	65	0.02	4	70	5660	25	<20	87	0.01	<10	8	10	<1	6939

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5468S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5469

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07036
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	G34516	0.33	0.010		
2	G34517	<0.03	<0.001		
3	G34518	<0.03	<0.001		
4	G34519	<0.03	<0.001		
5	G34520	0.54	0.016		
6	G34521	0.90	0.026		
7	G34522	0.58	0.017		
8	G34523	2.77	0.081		
9	G34524	0.17	0.005		
10	G34525	0.51	0.015	45.9	1.34
11	G34526	<0.03	<0.001		
12	G34527	0.70	0.020		
13	G34528	0.25	0.007		
14	G34529	0.43	0.013		
15	G34530	0.23	0.007		
16	G34531	0.58	0.017		
17	G34532	0.19	0.006		
18	G34533	0.15	0.004		
19	G34534	0.29	0.008		
20	G34535	0.21	0.006		
21	G34536	1.07	0.031		
22	G34537	0.50	0.015		
23	G34538	0.35	0.010		
24	G34539	0.34	0.010		
25	G34540	1.81	0.053		
26	G34541	0.22	0.006		
27	G34542	0.34	0.010		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 5469 17-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
28	G34543	0.25	0.007		
29	G34544	0.20	0.006		
30	G34545	0.29	0.008		
31	G34546	0.26	0.008		
32	G34547	0.22	0.006		
33	G34548	0.18	0.005		
34	G34549	0.31	0.009		
35	G34550	0.18	0.005		
QC DATA:					
Repeat:					
1	G34516	0.29	0.008		
5	G34520	0.57	0.017		
6	G34521	0.82	0.024		
8	G34523	2.94	0.086		
10	G34525	0.50	0.015	46.4	1.35
19	G34534	0.31	0.009		
21	G34536	1.11	0.032		
Resplits:					
1	G34516	0.27	0.008		
Standard:					
SI25		1.79	0.052		
Pb113				21.7	0.63

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

10-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5469

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07036
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34516	2.6	1.65	10	90	<5	2.27	<1	16	107	891	3.49	<10	1.49	1071	11	0.01	19	920	62	<5	<20	38	0.12	<10	23	<10	4	75
2	G34517	0.2	3.29	45	125	25	3.36	1	41	179	68	4.47	<10	4.09	1152	8	0.04	111	510	56	35	<20	129	0.22	<10	101	<10	7	61
3	G34518	0.2	3.07	55	225	10	1.97	<1	37	149	57	3.89	<10	3.88	806	5	0.04	70	750	52	25	<20	198	0.22	<10	84	<10	6	45
4	G34519	0.3	3.13	35	70	35	4.20	1	38	174	55	4.03	<10	4.06	1129	9	0.04	78	620	52	40	<20	156	0.19	<10	87	<10	6	49
5	G34520	5.3	0.97	15	100	<5	2.44	1	11	121	1414	2.52	<10	0.70	904	23	0.02	12	830	42	20	<20	55	0.05	<10	19	<10	5	71
6	G34521	1.8	0.77	10	200	<5	2.51	2	7	110	1048	2.06	<10	0.45	778	21	0.02	5	870	34	<5	<20	69	0.06	<10	18	<10	7	64
7	G34522	1.7	0.70	10	175	<5	2.81	<1	9	106	2000	2.06	<10	0.41	751	14	0.02	3	740	28	5	<20	74	0.05	<10	16	<10	6	52
8	G34523	2.4	0.58	40	60	<5	2.11	<1	9	87	1271	2.28	<10	0.27	669	11	0.01	3	970	32	<5	<20	47	0.05	<10	11	<10	6	38
9	G34524	1.9	0.89	<5	380	<5	2.25	<1	8	102	1792	2.81	<10	0.60	760	20	0.05	2	920	26	<5	<20	194	0.09	<10	40	<10	6	67
10	G34525	>30	0.77	10	55	<5	1.64	6	13	113	5439	4.53	<10	0.49	766	13	0.02	8	640	228	5	<20	44	0.05	<10	25	<10	4	313
11	G34526	<0.2	1.08	20	265	<5	0.61	<1	7	89	9	2.26	<10	0.64	555	6	0.13	11	890	20	5	<20	90	0.11	<10	49	<10	5	42
12	G34527	3.2	0.77	5	80	<5	1.79	2	10	80	1093	3.06	<10	0.51	816	9	0.02	4	920	86	<5	<20	54	0.06	<10	25	<10	5	112
13	G34528	1.3	0.88	<5	365	<5	2.48	1	8	117	1094	3.23	<10	0.60	869	12	0.04	8	940	22	5	<20	132	0.07	<10	40	<10	5	62
14	G34529	1.3	0.76	<5	180	<5	2.10	<1	8	98	1279	2.69	<10	0.50	741	20	0.03	5	830	22	<5	<20	109	0.06	<10	33	<10	5	59
15	G34530	0.8	0.65	10	430	<5	3.38	<1	7	100	740	2.51	<10	0.32	792	29	0.04	4	1000	20	<5	<20	190	0.08	<10	35	<10	7	40
16	G34531	1.9	0.75	20	145	<5	1.53	<1	10	132	2321	3.11	<10	0.47	644	32	0.04	5	860	22	<5	<20	88	0.06	<10	34	<10	5	67
17	G34532	0.8	0.73	<5	265	<5	2.22	<1	8	90	931	3.01	<10	0.45	670	16	0.04	5	980	20	<5	<20	133	0.07	<10	43	<10	5	47
18	G34533	0.5	0.88	<5	365	<5	2.58	<1	8	144	625	2.85	<10	0.58	809	162	0.05	6	970	26	<5	<20	183	0.09	<10	44	<10	6	62
19	G34534	1.4	0.86	10	315	<5	2.86	<1	8	110	1054	3.00	<10	0.54	896	17	0.04	7	970	22	5	<20	153	0.06	<10	37	<10	5	68
20	G34535	1.3	0.79	<5	240	<5	2.83	1	8	101	916	2.36	<10	0.43	813	45	0.02	3	970	52	<5	<20	135	0.07	<10	21	<10	8	104
21	G34536	2.2	0.76	20	85	<5	2.94	1	10	111	1048	2.21	<10	0.42	998	17	0.01	4	970	74	5	<20	94	0.06	<10	15	<10	7	123
22	G34537	2.7	0.70	25	60	<5	3.82	2	10	85	1250	3.02	<10	0.39	1253	35	0.02	6	980	38	15	<20	116	0.06	<10	15	<10	8	53
23	G34538	3.3	0.75	<5	75	<5	3.78	<1	13	110	2986	2.69	<10	0.43	996	22	0.02	1	770	38	<5	<20	158	0.06	<10	17	<10	7	75
24	G34539	1.1	2.21	20	70	<5	4.03	3	13	89	438	6.68	<10	1.63	1997	30	0.02	10	620	60	20	<20	216	0.10	<10	30	<10	4	292
25	G34540	3.9	1.15	30	60	<5	1.04	3	23	59	8594	4.15	20	0.67	209	635	0.05	67	60	72	25	<20	61	0.02	<10	44	<10	7	71

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34541	3.7	0.71	20	65	<5	0.69	15	10	180	2205	2.25	<10	0.42	474	74	0.01	6	790	44	<5	<20	27	0.05	<10	14	10	6	652
27	G34542	2.0	0.93	25	80	<5	0.48	<1	13	136	1105	2.87	<10	0.54	515	87	0.02	5	1030	30	<5	<20	19	0.06	<10	19	<10	4	55
28	G34543	1.1	0.87	10	85	<5	0.56	<1	11	120	695	2.33	<10	0.55	506	44	0.02	6	900	24	<5	<20	24	0.05	<10	17	<10	5	54
29	G34544	1.3	0.94	25	180	<5	1.88	<1	8	208	935	2.11	<10	0.53	698	81	0.03	5	860	50	<5	<20	110	0.07	<10	20	<10	8	49
30	G34545	1.2	0.92	20	295	<5	1.67	<1	7	208	1168	2.52	<10	0.55	591	96	0.05	7	830	26	<5	<20	129	0.07	<10	30	<10	7	47
31	G34546	1.6	0.80	10	110	<5	1.89	<1	9	167	965	2.85	<10	0.41	621	72	0.04	7	1030	28	<5	<20	100	0.07	<10	26	<10	7	48
32	G34547	4.1	0.92	20	85	<5	3.05	<1	9	188	1007	2.40	<10	0.56	1075	107	0.02	6	940	32	<5	<20	76	0.06	<10	17	<10	8	55
33	G34548	2.7	1.01	25	80	<5	2.61	1	13	150	733	2.99	<10	0.66	1131	38	0.02	10	1050	36	20	<20	72	0.06	<10	21	<10	7	64
34	G34549	2.5	0.90	25	80	<5	3.33	<1	13	175	1091	2.83	<10	0.54	1008	101	0.02	7	890	126	5	<20	107	0.07	<10	19	<10	8	72
35	G34550	0.9	0.86	10	195	<5	4.36	<1	9	140	529	2.82	<10	0.48	1102	40	0.03	4	900	34	<5	<20	191	0.07	<10	28	<10	6	70
QC DATA:																													
Repeat:																													
1	G34516	2.6	1.75	30	105	<5	2.35	1	18	113	933	3.59	<10	1.57	1102	14	0.02	23	980	68	15	<20	38	0.11	<10	25	<10	8	77
10	G34525	>30	0.80	10	50	<5	1.67	6	13	118	5565	4.60	<10	0.50	781	13	0.03	8	620	230	10	<20	41	0.04	<10	26	<10	4	310
19	G34534	1.4	0.87	10	330	<5	2.89	<1	9	114	1023	3.04	<10	0.53	900	17	0.04	6	1000	22	<5	<20	156	0.07	<10	38	<10	7	71
Resplit:																													
1	G34516	2.2	1.71	30	100	<5	2.31	2	19	114	874	3.69	<10	1.56	1178	11	0.01	20	910	64	25	<20	40	0.10	<10	25	<10	6	81
Standard:																													
Pb113		11.0	0.27	45	65	<5	1.73	37	3	7	2206	1.07	<10	0.11	1468	88	0.02	4	80	5564	25	<20	84	<0.01	<10	8	40	<1	6968

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5469S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5472

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07032
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34446	0.35	0.010
2	G34447	0.67	0.020
3	G34448	0.68	0.020
4	G34449	0.44	0.013
5	G34450	0.74	0.022
6	G34451	0.46	0.013
7	G34452	0.84	0.024
8	G34453	0.61	0.018
9	G34454	0.30	0.009
10	G34455	0.70	0.020
11	G34456	1.06	0.031
12	G34457	0.39	0.011
13	G34458	0.44	0.013
14	G34459	0.25	0.007
15	G34460	<0.03	<0.01
16	G34461	0.36	0.010
17	G34462	0.30	0.009
18	G34463	0.35	0.010
19	G34464	0.33	0.010
20	G34465	0.23	0.007
21	G34466	0.55	0.016
22	G34467	0.64	0.019
23	G34468	0.60	0.017
24	G34469	0.63	0.018
25	G34470	0.35	0.010
26	G34471	0.84	0.024
27	G34472	0.66	0.019

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 5472 17-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G34473	0.43	0.013
29	G34474	0.27	0.008
30	G34475	0.19	0.006
31	G34476	0.43	0.013
32	G34477	0.53	0.015
33	G34478	0.58	0.017
34	G34479	0.31	0.009
35	G34480	0.24	0.007

QC DATA:

Repeat:

1	G34446	0.37	0.011
3	G34448	0.67	0.020
5	G34450	0.73	0.021
10	G34455	0.62	0.018
11	G34456	1.19	0.035
19	G34464	0.34	0.010
20	G34465	0.26	0.008
21	G34466	0.59	0.017
22	G34467	0.68	0.020
25	G34470	0.36	0.010
26	G34471	0.82	0.024

Resplits:

1	G34446	0.43	0.013

Standard:

SI25		1.79	0.052

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

17-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5472

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07032
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34446	2.0	0.90	10	200	<5	2.40	<1	7	86	1251	2.84	<10	0.51	1118	20	0.01	5	1070	28	<5	<20	223	0.03	<10	18	<10	4	53
2	G34447	3.0	0.96	10	145	<5	1.90	<1	11	70	2020	3.16	<10	0.62	948	15	<0.01	5	950	30	<5	<20	172	0.02	<10	15	<10	4	58
3	G34448	2.2	1.06	10	80	<5	1.49	<1	10	88	1795	3.43	<10	0.70	689	23	<0.01	6	980	30	10	<20	114	0.02	<10	20	<10	3	50
4	G34449	1.7	0.76	10	45	<5	1.67	1	13	79	1260	3.87	<10	0.49	728	15	0.01	6	900	22	5	<20	100	0.02	<10	15	<10	<1	47
5	G34450	2.5	0.72	<5	85	<5	2.24	<1	8	82	2122	3.71	<10	0.54	657	13	0.03	3	770	20	<5	<20	224	0.02	<10	25	<10	3	47
6	G34451	1.4	0.89	<5	70	<5	1.59	1	16	66	1307	4.54	<10	0.73	554	13	0.03	6	970	26	<5	<20	118	0.04	<10	26	<10	5	48
7	G34452	2.5	0.76	<5	75	<5	2.63	1	11	85	2134	3.90	<10	0.66	789	18	0.04	4	830	26	<5	<20	405	0.04	<10	37	<10	4	49
8	G34453	2.2	0.78	15	75	<5	1.96	2	14	74	2168	3.70	<10	0.71	706	21	0.03	7	890	26	15	<20	121	0.03	<10	29	<10	6	49
9	G34454	1.0	0.68	5	210	<5	2.26	1	8	60	981	3.44	<10	0.57	744	12	0.03	6	960	22	<5	<20	211	0.04	<10	35	<10	5	45
10	G34455	1.6	0.86	15	85	<5	1.74	<1	15	80	1585	3.93	<10	0.66	653	17	0.02	5	970	30	<5	<20	113	0.04	<10	22	<10	6	50
11	G34456	2.3	0.88	10	95	<5	2.15	<1	10	83	2315	3.53	<10	0.64	606	14	0.02	6	900	34	<5	<20	161	0.02	<10	20	<10	7	50
12	G34457	1.2	0.95	10	265	<5	2.39	<1	7	91	1164	2.92	<10	0.60	835	17	0.01	4	1120	24	<5	<20	179	0.02	<10	16	<10	5	64
13	G34458	1.6	0.84	<5	90	<5	2.28	<1	8	82	1399	3.27	<10	0.52	889	17	0.01	5	1030	20	<5	<20	150	0.02	<10	15	<10	4	58
14	G34459	0.8	0.71	5	350	<5	3.68	<1	8	91	910	3.19	<10	0.48	1097	13	0.03	5	890	18	5	<20	312	0.05	<10	22	<10	5	43
15	G34460	<0.2	1.04	15	245	25	0.67	<1	8	98	5	2.19	<10	0.60	540	2	0.10	6	950	26	<5	<20	121	0.12	<10	46	<10	4	43
16	G34461	1.7	0.78	10	130	<5	3.31	2	8	83	1487	3.13	<10	0.52	989	13	0.02	6	860	20	5	<20	255	0.02	<10	18	<10	5	97
17	G34462	1.1	0.84	40	100	<5	2.89	1	11	67	918	2.68	<10	0.47	966	20	0.01	5	1060	26	5	<20	136	0.02	<10	12	<10	6	62
18	G34463	1.1	0.67	<5	135	<5	2.82	1	8	80	1042	2.60	<10	0.34	807	14	0.02	3	1090	20	<5	<20	179	0.03	<10	17	<10	5	39
19	G34464	1.2	0.66	15	150	<5	4.45	<1	8	89	1133	2.34	<10	0.36	1263	12	0.01	4	960	22	<5	<20	280	0.03	<10	15	<10	7	41
20	G34465	0.8	0.73	5	140	<5	4.09	<1	8	94	890	2.66	<10	0.44	1220	12	0.02	5	990	24	<5	<20	272	0.03	<10	16	<10	7	48
21	G34466	2.0	0.85	20	80	<5	3.41	<1	10	85	2073	3.56	<10	0.56	1034	10	0.01	3	830	24	<5	<20	205	0.03	<10	17	<10	5	60
22	G34467	3.1	1.05	15	80	<5	2.11	1	13	112	3706	3.81	<10	0.71	760	17	0.01	7	660	26	5	<20	115	0.01	<10	19	<10	5	52
23	G34468	2.0	1.03	20	100	<5	2.67	<1	9	74	1958	3.39	<10	0.63	934	12	0.01	4	950	28	<5	<20	136	0.02	<10	16	<10	6	53
24	G34469	1.9	1.07	10	150	<5	2.92	<1	8	86	1366	2.97	<10	0.61	1151	17	<0.01	6	980	32	10	<20	128	0.03	<10	18	<10	7	60
25	G34470	11.9	0.92	<5	90	<5	3.19	<1	10	106	1498	2.74	<10	0.56	1391	16	0.01	4	960	48	<5	<20	125	0.04	<10	13	<10	7	71

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007- 5472 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34471	21.1	0.83	25	55	<5	5.88	23	13	167	2393	3.99	<10	0.56	2482	20	0.01	7	620	1014	10	<20	256	0.05	<10	16	<10	4	1160
27	G34472	3.2	0.71	10	195	<5	2.91	1	9	91	1758	3.05	<10	0.47	885	17	0.02	6	930	24	5	<20	258	0.05	<10	28	<10	6	49
28	G34473	1.6	0.78	10	225	<5	2.37	2	11	89	1575	3.75	<10	0.58	852	11	0.03	6	900	30	5	<20	216	0.07	<10	39	<10	7	82
29	G34474	3.3	1.19	30	75	<5	1.01	4	23	50	2659	3.55	20	0.68	201	216	0.04	16	480	64	15	<20	53	0.03	<10	50	<10	8	280
30	G34475	0.7	0.73	10	380	<5	2.59	<1	9	84	656	3.12	<10	0.49	823	13	0.03	6	1100	24	5	<20	309	0.07	<10	36	<10	8	55
31	G34476	2.3	0.68	35	65	<5	2.13	<1	12	96	2380	2.84	<10	0.48	644	11	0.01	6	980	30	<5	<20	124	0.06	<10	19	<10	8	32
32	G34477	1.5	0.87	20	105	<5	2.54	<1	9	94	1349	2.87	<10	0.64	1020	13	0.01	6	950	26	10	<20	134	0.06	<10	18	<10	5	48
33	G34478	1.9	0.69	15	135	<5	2.80	<1	10	86	1297	2.81	<10	0.42	1032	11	0.01	5	990	28	<5	<20	140	0.06	<10	17	<10	8	41
34	G34479	1.0	0.76	10	185	<5	2.91	<1	11	81	703	2.98	<10	0.47	1080	13	0.02	4	1150	26	<5	<20	151	0.08	<10	22	<10	9	45
35	G34480	0.8	0.77	25	415	<5	2.63	<1	9	70	662	3.66	<10	0.55	925	18	0.03	3	1080	24	<5	<20	199	0.08	<10	39	<10	7	59
QC DATA:																													
Repeat:																													
1	G34446	2.0	0.90	10	195	<5	2.39	<1	7	84	1270	2.84	<10	0.51	1121	19	0.01	3	1060	26	<5	<20	232	0.03	<10	17	<10	4	52
10	G34455	1.6	0.82	10	75	<5	1.70	3	15	78	1508	3.83	<10	0.66	635	20	0.02	9	950	28	20	<20	99	0.02	<10	23	<10	5	50
19	G34464	1.1	0.71	10	160	<5	4.59	<1	9	91	1199	2.42	<10	0.38	1305	20	0.01	4	1010	24	<5	<20	298	0.04	<10	16	<10	8	42
Resplit:																													
1	G34446	2.7	1.00	20	185	<5	2.28	<1	10	83	1274	2.91	<10	0.50	1091	17	0.01	6	1100	30	5	<20	216	0.03	<10	18	<10	6	59
Standard:																													
Pb113		11.6	0.27	40	65	<5	1.76	39	3	6	2269	1.08	<10	0.12	1490	90	0.02	4	80	5504	20	<20	83	<0.01	<10	9	<10	<1	6951

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl/
dl/5469S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5473

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07033
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34481	0.24	0.007
2	G34482	0.22	0.006
3	G34483	0.17	0.005
4	G34484	0.10	0.003
5	G34485	0.14	0.004
6	G34486	0.16	0.005
7	G34487	0.11	0.003
8	G34488	0.14	0.004
9	G34489	0.25	0.007
10	G34490	0.35	0.010
11	G34491	0.24	0.007
12	G34492	0.24	0.007
13	G34493	0.29	0.008
14	G34494	0.22	0.006
15	G34495	0.95	0.028
16	G34496	0.36	0.010
17	G34497	0.76	0.022
18	G34498	<0.03	<0.001
19	G34499	0.83	0.024
20	G34500	0.37	0.011
21	G34501	0.54	0.016
22	G34502	0.26	0.008
23	G34503	0.14	0.004
24	G34504	0.68	0.020
25	G34505	0.51	0.015
26	G34506	0.34	0.010
27	G34507	0.29	0.008

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 5473 17-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G34508	0.43	0.013
29	G34509	0.38	0.011
30	G34510	0.88	0.026
31	G34511	0.73	0.021
32	G34512	0.64	0.019
33	G34513	0.97	0.028
34	G34514	0.60	0.017
35	G34515	0.60	0.017

QC DATA:

Repeat:

1	G34481	0.26	0.008
10	G34490	0.32	0.009
19	G34499	0.85	0.025

Resplits:

1	G34481	0.26	0.008

Standard:

SI25		1.76	0.051

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

1 g-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5473

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07033
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34481	0.9	0.82	25	180	<5	1.97	<1	11	88	742	3.49	<10	0.58	763	14	0.03	6	1100	36	<5	<20	123	0.08	<10	36	10	8	65
2	G34482	0.9	0.63	20	640	<5	2.50	<1	7	85	924	3.39	<10	0.41	765	21	0.04	5	1000	22	<5	<20	305	0.07	<10	49	<10	7	50
3	G34483	0.8	0.77	10	275	<5	1.87	<1	8	86	822	2.99	<10	0.56	691	14	0.04	3	900	28	<5	<20	238	0.07	<10	34	<10	5	56
4	G34484	0.4	0.91	10	690	<5	2.49	2	7	77	479	3.70	<10	0.69	898	17	0.04	8	1150	24	15	<20	303	0.08	<10	46	<10	7	67
5	G34485	0.7	0.79	20	205	<5	1.72	<1	10	72	760	3.36	<10	0.53	686	16	0.04	5	1050	28	<5	<20	126	0.09	<10	37	<10	8	59
6	G34486	0.7	0.77	10	255	<5	2.23	<1	9	103	821	3.20	<10	0.49	783	13	0.04	6	1000	24	<5	<20	238	0.08	<10	35	<10	7	59
7	G34487	0.6	0.69	15	555	<5	2.86	4	6	71	664	3.16	<10	0.43	861	9	0.04	4	1040	22	<5	<20	318	0.08	<10	40	<10	8	50
8	G34488	0.6	0.71	20	520	<5	2.76	<1	6	70	826	3.38	<10	0.48	877	17	0.04	6	990	22	<5	<20	303	0.08	<10	43	<10	6	57
9	G34489	0.9	0.74	25	100	<5	2.15	<1	10	68	864	3.06	<10	0.52	820	22	0.03	4	1000	28	<5	<20	202	0.07	<10	26	<10	5	54
10	G34490	1.1	0.73	20	120	<5	1.72	1	12	64	1183	3.29	<10	0.51	622	11	0.02	5	940	26	<5	<20	87	0.06	<10	30	<10	5	65
11	G34491	1.2	0.64	25	90	<5	1.30	<1	10	63	1108	2.94	<10	0.43	513	13	0.02	5	1000	28	<5	<20	66	0.06	<10	24	<10	6	39
12	G34492	0.9	0.74	20	80	<5	2.33	<1	8	76	796	2.33	<10	0.50	857	9	0.01	5	970	18	<5	<20	99	0.06	<10	16	<10	5	45
13	G34493	2.1	0.55	40	50	<5	2.31	<1	12	100	1447	2.69	<10	0.33	727	12	0.01	5	860	36	<5	<20	83	0.05	<10	11	<10	5	32
14	G34494	2.2	0.63	35	85	<5	2.38	<1	8	100	1046	2.11	<10	0.37	859	14	0.01	5	980	24	<5	<20	98	0.05	<10	11	<10	7	45
15	G34495	3.0	0.47	20	70	<5	3.48	1	15	108	1721	3.53	<10	0.22	1123	12	0.01	7	890	34	10	<20	152	0.05	<10	11	<10	7	33
16	G34496	3.1	0.78	25	75	<5	3.07	<1	8	77	827	2.26	<10	0.53	1253	16	<0.01	5	1090	28	5	<20	140	0.06	<10	12	<10	5	81
17	G34497	7.8	0.27	30	65	<5	2.91	20	14	90	1288	4.29	<10	0.05	932	19	0.01	6	760	176	10	<20	140	0.07	<10	7	<10	5	926
18	G34498	<0.2	1.04	30	275	25	0.59	<1	8	104	6	2.23	<10	0.63	561	3	0.11	7	980	28	10	<20	90	0.13	<10	49	<10	5	45
19	G34499	3.5	0.29	40	45	<5	7.84	<1	10	86	856	3.14	<10	0.11	2306	9	0.01	5	700	66	<5	<20	356	0.07	<10	7	<10	6	34
20	G34500	3.5	0.93	15	80	<5	3.97	<1	8	103	1451	2.62	<10	0.73	1505	10	<0.01	2	770	24	<5	<20	149	0.06	<10	15	<10	4	80
21	G34501	3.9	1.21	30	70	<5	3.37	2	11	132	1643	4.24	<10	0.83	1480	14	0.01	9	800	34	10	<20	138	0.06	<10	40	<10	4	87
22	G34502	1.3	0.87	10	165	<5	2.48	1	8	65	885	2.68	<10	0.55	949	16	0.01	5	1170	26	5	<20	118	0.05	<10	19	<10	7	70
23	G34503	0.7	0.66	25	140	<5	3.60	<1	7	92	542	2.55	<10	0.32	1084	10	0.01	5	1020	22	<5	<20	171	0.05	<10	16	<10	3	45
24	G34504	1.9	0.74	25	105	<5	3.33	<1	10	85	1654	2.38	<10	0.43	1001	11	0.01	4	880	30	<5	<20	156	0.05	<10	14	<10	5	49
25	G34505	1.9	0.72	20	140	<5	3.14	<1	9	85	2077	2.71	<10	0.39	839	10	0.02	5	920	32	<5	<20	167	0.05	<10	20	<10	6	42

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34506	1.6	0.85	20	105	<5	3.30	2	11	111	1613	3.18	<10	0.48	1028	13	0.02	8	990	50	15	<20	177	0.05	<10	19	<10	6	56
27	G34507	3.3	0.83	25	105	<5	3.22	1	10	109	1147	3.15	<10	0.42	986	14	0.01	6	1060	46	<5	<20	127	0.06	<10	19	<10	5	55
28	G34508	3.9	1.22	30	100	<5	2.89	2	11	97	1510	3.65	<10	0.76	1194	12	0.01	5	1170	134	10	<20	95	0.09	<10	16	<10	7	132
29	G34509	1.1	1.24	20	125	<5	1.77	<1	15	24	3994	3.59	<10	1.15	750	8	0.17	15	1100	36	15	<20	178	0.13	<10	180	<10	8	46
30	G34510	2.9	1.15	25	110	<5	4.06	1	10	113	3030	3.24	<10	0.66	1339	13	0.01	7	710	34	10	<20	129	0.06	<10	18	<10	4	67
31	G34511	3.6	0.81	25	70	<5	2.99	<1	10	112	2929	2.88	<10	0.55	1076	9	0.01	5	520	28	<5	<20	61	0.04	<10	15	<10	3	49
32	G34512	9.1	0.76	35	45	<5	2.21	4	12	103	1289	4.73	<10	0.51	968	17	0.01	9	910	182	5	<20	41	0.06	<10	17	<10	4	212
33	G34513	4.9	0.96	35	75	<5	2.53	<1	11	113	1377	3.91	<10	0.55	922	10	0.01	7	880	70	<5	<20	45	0.05	<10	19	<10	3	80
34	G34514	4.7	0.99	30	85	<5	2.50	4	10	100	1072	3.39	<10	0.60	1037	17	0.01	4	950	68	<5	<20	46	0.06	<10	17	<10	5	253
35	G34515	7.1	0.90	30	55	<5	1.49	2	11	108	2236	3.82	<10	0.65	793	13	0.01	6	860	60	5	<20	28	0.05	<10	19	<10	4	139
QC DATA:																													
Repeat:																													
1	G34481	1.0	0.85	20	180	<5	1.96	<1	11	90	746	3.47	<10	0.59	761	14	0.03	5	1060	32	<5	<20	117	0.08	<10	36	<10	7	63
10	G34490	1.1	0.77	15	130	<5	1.80	2	13	68	1226	3.44	<10	0.54	646	14	0.03	7	990	30	15	<20	97	0.06	<10	32	<10	7	68
19	G34499	3.7	0.30	40	50	<5	8.03	<1	10	90	881	3.17	<10	0.11	2361	9	0.01	3	730	66	<5	<20	377	0.08	<10	7	<10	8	36
Resplit:																													
1	G34481	1.2	0.83	15	165	<5	1.88	1	11	96	751	3.55	<10	0.57	724	14	0.03	8	1130	34	10	<20	118	0.07	<10	36	<10	5	63
Standard:																													
Pb113		11.6	0.28	45	60	<5	1.60	40	2	6	2253	1.11	<10	0.11	1524	96	0.02	6	90	5502	20	<20	88	<0.01	<10	11	<10	<1	6948

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
dl/5469S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5474

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07034
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36501	0.16	0.005
2	G36502	0.19	0.006
3	G36503	0.16	0.005
4	G36504	0.16	0.005
5	G36505	0.14	0.004
6	G36506	0.13	0.004
7	G36507	0.14	0.004
8	G36508	0.99	0.029
9	G36509	0.19	0.006
10	G36510	0.21	0.006
11	G36511	0.15	0.004
12	G36512	0.17	0.005
13	G36513	0.17	0.005
14	G36514	0.18	0.005
15	G36515	0.26	0.008
16	G36516	0.19	0.006
17	G36517	0.59	0.017
18	G36518	0.13	0.004
19	G36519	<0.03	<0.001
20	G36520	0.13	0.004
21	G36521	0.08	0.002
22	G36522	0.41	0.012
23	G36523	0.17	0.005
24	G36524	0.35	0.010
25	G36525	0.13	0.004
26	G36526	0.19	0.006
27	G36527	0.13	0.004

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 5474 17-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G36528	0.14	0.004
29	G36529	0.13	0.004
30	G36530	0.19	0.006
31	G36531	0.13	0.004
32	G36532	0.15	0.004
33	G36533	0.94	0.027
34	G36534	0.19	0.006
35	G36535	0.21	0.006

QC DATA:

Repeat:

1	G36501	0.18	0.005
10	G36510	0.21	0.006
20	G36520	0.11	0.003

Resplits:

1	G36501	0.18	0.005

Standard:

SI25		1.80	0.052

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

17-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5474

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07034
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36501	0.8	0.73	15	30	<5	2.29	<1	20	95	941	4.13	<10	0.62	441	150	0.03	14	1200	58	<5	<20	99	0.02	<10	29	<10	3	42
2	G36502	0.9	1.11	15	45	<5	1.37	<1	17	62	863	4.20	<10	0.93	348	85	0.02	6	1600	36	<5	<20	61	0.02	<10	36	<10	4	37
3	G36503	0.8	1.21	15	55	<5	2.13	<1	18	50	813	4.01	<10	1.15	513	72	0.03	6	1490	52	5	<20	86	0.03	<10	44	<10	5	68
4	G36504	0.7	1.27	15	40	<5	1.55	1	14	68	688	3.88	<10	1.09	397	104	0.02	8	1700	34	15	<20	64	0.02	<10	43	<10	4	42
5	G36505	0.6	1.15	20	50	<5	2.84	<1	15	72	746	3.84	<10	0.96	492	202	0.03	7	1550	38	10	<20	118	0.02	<10	38	<10	7	35
6	G36506	0.5	0.89	10	55	<5	2.16	1	18	71	790	3.55	<10	0.75	379	56	0.03	9	1590	42	10	<20	91	0.02	<10	33	<10	6	42
7	G36507	0.4	1.24	30	50	<5	2.27	<1	14	75	628	3.75	<10	1.17	460	113	0.02	6	1660	52	5	<20	74	0.04	<10	39	<10	6	86
8	G36508	3.7	1.19	80	85	<5	0.79	4	19	62	3261	3.93	20	0.56	272	221	0.04	16	380	150	30	<20	39	0.03	<10	48	<10	7	167
9	G36509	0.6	0.77	25	40	<5	3.01	<1	18	63	873	3.86	<10	0.65	479	518	0.02	5	1450	42	5	<20	113	0.02	<10	26	<10	4	53
10	G36510	0.5	0.98	25	50	<5	1.71	<1	16	66	757	3.48	<10	0.84	332	71	0.03	6	1700	36	10	<20	90	0.02	<10	38	<10	5	45
11	G36511	0.6	0.76	<5	35	<5	2.30	2	20	96	903	3.99	<10	0.63	378	79	0.02	10	1500	38	15	<20	98	<0.01	<10	30	<10	4	35
12	G36512	0.5	1.24	25	55	<5	1.10	<1	13	77	557	3.53	<10	1.13	282	56	0.04	7	1700	34	15	<20	76	0.02	<10	53	<10	6	39
13	G36513	0.4	1.07	15	40	<5	1.48	<1	16	75	636	3.97	<10	0.95	341	45	0.03	5	1750	38	<5	<20	78	0.02	<10	40	<10	5	36
14	G36514	0.6	1.13	25	45	<5	0.74	<1	17	74	738	3.89	<10	0.95	257	104	0.03	6	1660	34	5	<20	113	0.02	<10	43	<10	5	46
15	G36515	0.8	1.17	25	50	<5	1.44	<1	20	112	989	4.97	<10	0.98	306	180	0.04	8	1460	48	10	<20	83	0.03	<10	47	<10	5	38
16	G36516	1.2	1.01	15	55	<5	3.72	1	17	85	679	4.06	<10	0.92	587	38	0.02	7	1540	46	10	<20	127	0.03	<10	38	<10	6	71
17	G36517	3.6	0.89	30	40	<5	1.77	1	17	77	612	4.11	<10	0.77	415	62	0.01	7	1650	42	<5	<20	59	0.02	<10	37	<10	4	41
18	G36518	1.5	1.32	45	50	<5	2.33	<1	14	81	561	4.00	<10	1.22	517	125	0.02	8	1830	38	10	<20	84	0.03	<10	51	<10	7	44
19	G36519	<0.2	1.14	40	270	25	0.56	<1	9	90	6	2.20	<10	0.66	592	4	0.12	7	930	20	<5	<20	94	0.13	<10	52	<10	6	47
20	G36520	0.7	1.04	25	55	<5	2.48	<1	11	81	339	3.64	<10	0.94	511	43	0.02	7	1670	34	5	<20	87	0.02	<10	41	<10	5	46
21	G36521	0.7	1.15	30	45	<5	3.14	<1	15	68	434	3.98	<10	1.01	611	20	0.02	7	1690	36	5	<20	110	0.03	<10	41	<10	6	37
22	G36522	1.0	1.20	25	50	<5	2.35	2	15	52	410	3.79	<10	1.13	528	24	0.02	10	1670	32	25	<20	73	0.01	<10	47	<10	5	50
23	G36523	1.9	1.00	40	30	<5	2.41	<1	14	76	434	3.75	<10	0.88	542	44	0.02	7	1760	34	5	<20	101	0.03	<10	40	<10	5	42
24	G36524	0.8	1.00	35	50	<5	3.91	<1	13	56	333	3.57	<10	0.89	711	23	0.02	6	1760	30	5	<20	113	0.03	<10	43	<10	6	32
25	G36525	1.5	0.82	60	40	<5	1.87	<1	12	78	414	3.52	<10	0.65	392	60	0.01	7	1800	32	5	<20	108	0.02	<10	34	<10	7	32

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36526	1.3	0.97	25	35	<5	3.26	<1	13	63	485	3.74	<10	0.87	751	30	0.01	6	1740	34	5	<20	281	0.04	<10	39	<10	7	45
27	G36527	1.9	1.03	15	45	<5	2.88	1	17	89	602	4.83	<10	0.98	710	43	0.02	10	1510	40	10	<20	119	0.06	<10	43	<10	7	59
28	G36528	1.7	0.95	50	45	<5	3.67	1	27	86	527	4.98	<10	0.84	722	39	0.01	9	1750	32	5	<20	121	0.04	<10	41	<10	9	40
29	G36529	1.8	0.99	45	50	<5	3.65	<1	16	76	534	4.38	<10	0.91	819	42	0.01	6	1700	70	<5	<20	118	0.05	<10	40	<10	10	73
30	G36530	2.3	1.05	35	50	<5	5.18	1	24	78	552	5.59	<10	0.96	1037	53	0.02	10	1640	50	10	<20	152	0.05	<10	41	<10	9	55
31	G36531	1.5	1.07	30	55	<5	4.08	<1	17	86	593	4.62	<10	0.97	828	116	0.02	8	1680	48	15	<20	108	0.04	<10	41	<10	6	42
32	G36532	1.3	0.99	40	50	<5	4.04	<1	20	98	574	4.71	<10	0.83	753	46	0.01	10	1690	68	10	<20	116	0.04	<10	36	<10	9	30
33	G36533	2.0	0.89	60	70	<5	4.07	<1	20	80	523	4.40	<10	0.74	823	128	0.01	11	2000	68	25	<20	122	0.03	<10	36	<10	10	39
34	G36534	1.5	0.79	60	60	<5	3.35	<1	22	106	528	4.93	<10	0.61	573	60	0.01	8	1720	70	<5	<20	104	0.04	<10	30	<10	9	41
35	G36535	1.2	1.13	25	50	<5	4.05	1	25	60	591	5.09	<10	1.05	663	57	0.03	9	1640	52	10	<20	120	0.04	<10	45	<10	7	40
QC DATA:																													
Repeat:																													
1	G36501	0.8	0.76	15	45	<5	2.33	<1	22	98	970	4.20	<10	0.64	452	149	0.03	14	1240	64	<5	<20	106	0.02	<10	30	<10	5	43
10	G36510	0.5	1.01	35	40	<5	1.73	<1	16	67	765	3.52	<10	0.86	337	66	0.03	8	1720	34	10	<20	89	0.02	<10	40	<10	5	46
19	G36519	<0.2	1.19	35	295	30	0.69	<1	9	144	6	2.45	<10	0.68	605	4	0.13	7	1060	32	<5	<20	118	0.13	<10	56	<10	5	47
Resplit:																													
1	G36501	0.8	0.78	10	35	<5	2.29	<1	22	93	950	4.32	<10	0.63	450	139	0.03	15	1230	58	<5	<20	93	0.03	<10	37	<10	4	45
Standard:																													
Pb113		11.6	0.29	45	80	<5	1.66	40	5	9	2310	1.14	<10	0.12	1559	68	0.02	4	80	5580	30	<20	85	0.03	<10	12	<10	5	7081

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5469S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5477

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07035
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	G36536	0.23	0.007		
2	G36537	0.13	0.004		
3	G36538	0.15	0.004		
4	G36539	0.20	0.006		
5	G36540	0.03	0.001		
6	G36541	<0.03	<0.001		
7	G36542	0.04	0.001		
8	G36543	<0.03	<0.001		
9	G36544	<0.03	<0.001		
10	G36545	<0.03	<0.001		
11	G36546	0.28	0.008		
12	G36547	0.05	0.001		
13	G36548	0.06	0.002		
14	G36549	0.06	0.002		
15	G36550	0.09	0.003		
16	G36551	0.11	0.003		
17	G36552	0.13	0.004		
18	G36553	0.50	0.015		
19	G36554	1.80	0.052		
20	G36555	0.83	0.024	178	5.19
21	G36556	0.50	0.015		
22	G36557	0.20	0.006		
23	G36558	1.07	0.031		
24	G36559	0.38	0.011		
25	G36560	0.36	0.010		
26	G36561	<0.03	<0.001		
27	G36562	0.42	0.012		
28	G36563	0.26	0.008		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5477 17-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
29	G36564	0.24	0.007		
30	G36565	0.13	0.004		
31	G36566	0.13	0.004		
32	G36567	0.42	0.012		
33	G36568	0.52	0.015		
34	G36569	0.36	0.010		
35	G36570	0.17	0.005		
QC DATA:					
Repeat:					
1	G36536	0.26	0.008		
10	G36545	0.03	0.001		
20	G36555			183	5.34
23	G36558	1.02	0.030		
29	G36564	0.22	0.006		
33	G36568	0.55	0.016		
34	G36569	0.33	0.010		
Resplit:					
1	G36536	0.20	0.006		
Standard:					
Si25		1.79	0.052		
Pb113				21.7	0.63

AU: 30g FA/AA-Finish

ECO-TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

17-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5477

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07035
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36536	1.3	1.09	<5	50	<5	2.21	2	15	50	483	4.20	<10	1.09	460	42	0.02	7	1480	34	15	<20	61	0.03	<10	41	<10	3	35
2	G36537	0.9	1.24	<5	65	<5	2.88	1	10	45	340	3.44	<10	1.22	568	18	0.02	5	1500	28	10	<20	85	0.03	<10	47	<10	4	36
3	G36538	1.1	0.89	<5	60	<5	2.28	2	16	67	390	4.23	<10	0.85	386	22	0.02	7	1450	32	<5	<20	66	0.03	<10	33	<10	4	22
4	G36539	1.5	1.10	<5	55	<5	3.66	2	20	60	598	5.13	<10	1.12	615	11	0.02	8	1450	38	20	<20	100	0.03	<10	41	<10	3	27
5	G36540	0.3	0.80	10	290	<5	2.36	<1	9	26	48	2.30	10	0.43	994	5	<0.01	5	950	20	10	<20	68	0.02	<10	15	<10	6	44
6	G36541	0.3	0.72	5	215	<5	0.73	1	11	21	96	2.35	10	0.28	877	6	<0.01	6	980	20	<5	<20	12	0.02	<10	12	<10	5	60
7	G36542	0.2	0.47	<5	555	<5	0.87	1	8	16	104	2.60	20	0.14	1057	5	0.01	6	990	14	<5	<20	21	0.02	<10	10	<10	7	57
8	G36543	0.2	0.36	<5	625	<5	1.68	1	8	30	159	2.57	20	0.19	1258	6	0.01	9	910	6	<5	<20	49	0.02	<10	10	<10	7	71
9	G36544	0.3	0.44	5	175	<5	0.41	1	10	21	429	2.16	20	0.05	1065	7	0.01	12	970	14	<5	<20	2	0.02	<10	9	<10	10	85
10	G36545	0.4	0.45	5	270	<5	0.16	1	10	18	571	1.95	30	0.03	1403	13	<0.01	12	940	20	<5	<20	<1	0.02	<10	8	<10	10	80
11	G36546	3.3	0.49	<5	120	<5	0.12	2	14	39	980	2.71	<10	0.04	2725	32	0.02	17	900	126	5	<20	<1	0.02	<10	48	<10	3	53
12	G36547	2.7	0.47	<5	195	<5	0.50	1	11	41	948	2.69	20	0.12	2419	30	0.02	16	970	176	<5	<20	13	0.02	<10	41	<10	6	99
13	G36548	4.2	0.47	<5	135	<5	0.15	1	11	39	727	2.59	20	0.10	2143	18	0.02	15	810	270	<5	<20	<1	0.02	<10	46	<10	5	134
14	G36549	2.4	0.91	5	60	<5	0.61	1	11	48	865	3.79	10	0.51	1208	14	0.03	16	640	98	<5	<20	24	0.03	<10	97	<10	3	106
15	G36550	2.5	0.96	15	70	<5	0.83	2	12	44	1326	3.62	20	0.49	1429	21	0.02	24	940	174	5	<20	44	0.02	<10	84	<10	10	116
16	G36551	4.0	0.79	20	70	<5	0.83	2	13	47	1685	3.63	20	0.34	2422	27	0.01	28	1160	202	5	<20	36	0.03	<10	87	<10	10	99
17	G36552	3.4	0.56	10	45	<5	2.34	1	15	43	1204	3.18	10	0.30	1098	31	0.01	20	1050	182	<5	<20	117	0.02	<10	48	<10	4	34
18	G36553	6.9	0.78	25	70	<5	4.98	1	12	52	1438	4.47	10	0.19	2677	29	0.02	15	730	74	10	<20	174	0.04	<10	125	<10	5	43
19	G36554	4.0	1.09	25	55	<5	0.98	3	21	55	8609	4.01	10	0.69	195	554	0.04	63	60	66	20	<20	53	0.03	<10	40	<10	4	72
20	G36555	>30	2.03	470	80	<5	4.39	21	13	81	7803	5.77	10	0.52	1326	39	0.14	48	380	2604	2775	<20	92	0.02	<10	201	<10	3	1505
21	G36556	21.7	1.50	155	70	<5	4.19	32	13	90	3597	4.72	10	0.36	1731	58	0.05	42	390	2834	225	<20	105	0.03	<10	264	<10	1	5206
22	G36557	1.9	0.60	10	60	<5	3.64	2	11	52	462	3.31	<10	0.39	2374	10	<0.01	10	380	62	15	<20	141	0.03	<10	86	<10	1	33
23	G36558	1.6	0.70	15	55	<5	3.87	1	9	49	543	3.43	<10	0.51	2198	6	0.01	8	520	46	10	<20	148	0.03	<10	140	<10	1	32
24	G36559	2.3	0.92	85	65	<5	3.81	2	14	38	1015	3.57	<10	0.70	2126	10	0.01	10	1120	60	10	<20	149	0.04	<10	104	<10	3	34
25	G36560	1.0	1.01	40	65	<5	3.28	1	14	49	752	3.28	<10	0.83	1946	9	0.02	17	660	36	10	<20	132	0.05	<10	123	<10	2	43

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36561	<0.2	0.98	10	260	<5	0.50	<1	5	90	5	2.06	<10	0.55	508	3	0.09	6	880	20	5	<20	68	0.10	<10	42	<10	2	43
27	G36562	2.5	1.15	60	75	<5	4.01	<1	12	42	1751	2.95	<10	0.97	2090	8	0.02	19	840	48	10	<20	151	0.06	<10	185	<10	4	55
28	G36563	1.8	1.46	20	115	<5	6.19	1	19	48	876	4.51	<10	2.26	2149	14	0.04	23	750	42	15	<20	334	0.09	<10	683	<10	4	92
29	G36564	1.3	1.58	15	110	<5	3.93	1	16	49	878	4.03	<10	1.53	1630	8	0.03	20	750	44	10	<20	232	0.05	<10	373	<10	3	89
30	G36565	1.2	1.23	35	90	<5	2.75	1	19	51	854	3.57	<10	0.98	1150	7	0.02	12	750	40	10	<20	145	0.03	<10	256	<10	<1	67
31	G36566	0.8	0.63	30	75	<5	1.87	<1	6	62	392	1.61	<10	0.42	742	10	0.05	12	450	48	10	<20	104	0.02	<10	81	<10	1	31
32	G36567	0.9	0.53	15	65	<5	2.47	<1	7	48	585	1.86	<10	0.28	821	9	0.06	4	570	30	<5	<20	165	0.01	<10	123	<10	2	36
33	G36568	1.4	0.56	<5	65	<5	4.35	1	11	41	1295	2.17	10	0.48	1433	8	0.04	6	790	26	15	<20	254	0.01	<10	203	<10	6	37
34	G36569	4.6	1.33	<5	75	<5	4.54	2	14	50	1331	4.12	10	0.96	1858	8	0.03	22	1000	80	10	<20	243	0.04	<10	197	<10	5	81
35	G36570	1.8	0.75	5	55	<5	2.14	1	8	67	383	2.55	10	0.49	1197	11	0.03	16	610	52	10	<20	129	0.02	<10	89	<10	3	62
QC DATA:																													
Repeat:																													
1	G36536	1.2	1.07	<5	50	<5	2.20	2	15	50	476	4.14	<10	1.07	456	38	0.02	7	1500	34	15	<20	64	0.03	<10	40	<10	4	33
10	G36545	0.5	0.42	5	255	<5	0.17	<1	10	18	563	1.95	20	0.02	1401	13	<0.01	13	950	20	<5	<20	<1	0.02	<10	8	<10	9	81
Resplit:																													
1	G36536	1.0	1.04	<5	55	<5	2.53	2	14	56	478	3.88	<10	1.02	475	40	0.02	7	1490	34	10	<20	67	0.03	<10	39	<10	4	33
Standard:																													
Pb113		11.8	0.24	40	55	<5	1.69	39	1	5	2294	1.05	<10	0.10	1450	75	0.02	2	70	5460	20	<20	84	0.01	<10	6	<10	<1	6924

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5477S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5478

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07037
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36571	0.34	0.010
2	G36572	0.23	0.007
3	G36573	0.20	0.006
4	G36574	0.09	0.003
5	G36575	0.16	0.005
6	G36576	0.39	0.011
7	G36577	0.13	0.004
8	G36578	0.09	0.003
9	G36579	0.21	0.006
10	G36580	0.21	0.006
11	G36581	0.27	0.008
12	G36582	0.29	0.008
13	G36583	0.90	0.026
14	G36584	0.25	0.007
15	G36585	0.09	0.003
16	G36586	0.14	0.004
17	G36587	0.11	0.003
18	G36588	<0.03	<0.001
19	G36589	0.26	0.008
20	G36590	0.12	0.003
21	G36591	0.36	0.010
22	G36592	0.46	0.013
23	G36593	0.25	0.007
24	G36594	0.64	0.019
25	G36595	0.34	0.010
26	G36596	0.12	0.003
27	G36597	0.28	0.008
28	G36598	5.85	0.171

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 5478 17-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G36599	0.69	0.020
30	G36600	0.14	0.004
31	G36601	0.41	0.012
32	G36602	0.19	0.006
33	G36603	0.73	0.021
34	G36604	0.35	0.010
35	G36605	0.24	0.007

QC DATA:

Repeat:

1	G36571	0.33	0.010
13	G36583	0.93	0.027
10	G36580	0.19	0.006
19	G36589	0.30	0.009
28	G36598	6.10	0.178
29	G36599	0.73	0.021
33	G36603	0.67	0.020

Resplits:

1	G36571	0.32	0.009

Standard:

Si25		1.84	0.054

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

16-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5478

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07037
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36571	2.4	1.15	10	80	<5	2.86	2	16	76	644	3.53	20	0.89	1320	8	0.06	27	780	54	10	<20	171	0.04	<10	171	<10	5	77
2	G36572	3.2	0.94	15	85	<5	3.56	2	19	57	1013	2.92	20	0.46	1504	12	0.03	22	970	68	5	<20	199	0.03	<10	99	<10	6	78
3	G36573	2.1	0.72	5	70	<5	2.58	1	8	69	1449	2.07	20	0.34	1179	10	0.04	16	700	26	<5	<20	161	0.02	<10	97	<10	5	46
4	G36574	1.5	0.27	<5	75	<5	2.76	<1	5	54	537	1.29	10	0.05	1141	14	0.03	6	300	20	<5	<20	174	0.02	<10	19	<10	4	36
5	G36575	1.7	0.71	10	75	<5	3.54	<1	10	60	411	2.25	20	0.23	1533	6	0.06	14	670	26	<5	<20	212	0.03	<10	87	<10	6	36
6	G36576	8.4	1.01	10	55	<5	3.83	13	15	55	1449	3.62	20	0.52	1761	14	0.04	25	1170	632	10	<20	173	0.04	<10	100	20	8	1049
7	G36577	1.9	0.56	<5	55	<5	1.91	2	12	63	530	3.44	20	0.21	825	11	0.04	17	560	116	<5	<20	119	0.02	<10	73	<10	4	86
8	G36578	1.3	0.63	<5	55	<5	2.62	2	10	60	424	2.55	20	0.40	1500	8	0.05	13	540	42	<5	<20	162	0.03	<10	80	<10	4	64
9	G36579	1.5	0.78	<5	70	<5	2.81	1	12	69	577	2.87	20	0.59	2243	7	0.06	12	540	20	5	<20	183	0.04	<10	89	<10	3	22
10	G36580	1.6	0.85	<5	75	<5	2.63	<1	12	62	510	2.81	20	0.62	2211	6	0.06	12	560	20	<5	<20	193	0.05	<10	95	10	5	22
11	G36581	1.7	0.87	<5	80	<5	3.36	2	20	57	1100	3.32	20	0.59	1748	14	0.04	19	720	30	15	<20	204	0.03	<10	85	<10	6	35
12	G36582	1.8	0.65	10	60	<5	2.07	1	17	57	852	3.16	20	0.26	1065	26	0.04	16	550	34	<5	<20	137	0.03	<10	64	<10	3	33
13	G36583	1.5	0.74	10	65	<5	1.34	1	13	65	620	3.31	20	0.51	1381	18	0.05	16	470	22	<5	<20	101	0.03	<10	80	<10	3	50
14	G36584	1.5	0.76	20	65	<5	1.80	<1	11	68	624	3.35	20	0.62	1550	28	0.05	13	440	32	<5	<20	158	0.04	<10	84	<10	2	33
15	G36585	1.0	0.77	<5	65	<5	2.20	<1	11	70	439	2.92	20	0.55	1703	23	0.06	13	460	26	<5	<20	168	0.04	<10	75	<10	2	28
16	G36586	1.5	0.69	<5	45	<5	2.59	1	9	67	526	2.92	20	0.59	2370	15	0.06	13	420	32	<5	<20	168	0.04	<10	79	<10	2	50
17	G36587	1.5	0.88	<5	60	<5	2.26	1	7	67	402	2.92	20	0.78	2004	14	0.05	11	430	48	5	<20	171	0.04	<10	89	<10	3	68
18	G36588	<0.2	1.11	5	280	20	0.59	<1	6	79	5	2.17	<10	0.62	576	1	0.10	7	950	22	5	<20	86	0.14	<10	50	<10	3	43
19	G36589	1.5	0.93	<5	80	<5	2.10	1	10	61	601	3.33	20	0.80	1988	11	0.05	12	390	32	<5	<20	183	0.05	<10	100	<10	3	36
20	G36590	1.3	0.93	15	65	<5	2.20	<1	10	66	584	2.90	20	0.62	1275	15	0.06	12	380	58	10	<20	166	0.03	<10	78	<10	4	33
21	G36591	1.4	1.07	<5	80	<5	1.99	1	19	67	792	4.27	20	0.62	808	18	0.04	16	480	66	5	<20	136	0.04	<10	131	<10	3	43
22	G36592	1.0	0.82	10	65	<5	2.59	2	10	58	467	3.16	20	0.49	1219	22	0.05	14	490	52	15	<20	174	0.03	40	106	<10	4	39
23	G36593	1.0	1.34	30	105	<5	3.55	2	19	42	527	3.25	20	1.16	1299	31	0.05	25	1600	122	10	<20	246	0.08	<10	92	<10	9	64
24	G36594	0.9	1.45	10	90	<5	2.23	<1	18	47	661	3.34	20	1.41	772	22	0.06	19	1470	86	10	<20	187	0.07	<10	104	<10	7	59
25	G36595	0.8	0.97	15	80	<5	2.44	<1	9	46	482	2.59	10	0.68	710	10	0.06	4	1300	76	<5	<20	219	0.03	10	90	<10	6	32

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36596	0.6	1.91	10	105	<5	2.42	2	21	55	624	4.86	20	1.94	759	17	0.07	29	1670	74	15	<20	155	0.08	<10	164	<10	5	79
27	G36597	3.2	1.27	20	50	<5	1.05	2	22	53	2749	3.57	20	0.75	209	204	0.04	11	440	64	10	<20	68	0.05	<10	51	<10	7	269
28	G36598	1.4	1.55	20	140	<5	2.51	1	15	65	654	3.01	20	1.34	578	31	0.13	24	1280	72	10	<20	162	0.05	<10	166	<10	8	54
29	G36599	0.9	1.38	15	95	<5	2.60	<1	11	52	442	3.19	10	1.13	1061	7	0.05	6	1260	110	10	<20	226	0.04	<10	129	<10	7	65
30	G36600	2.4	1.14	20	85	<5	2.75	1	14	37	517	3.23	10	0.83	977	18	0.04	6	1340	408	10	<20	196	0.04	<10	69	<10	5	46
31	G36601	2.4	0.58	70	60	<5	3.13	2	13	37	390	3.63	20	0.18	1596	63	0.02	8	1340	284	60	<20	234	0.03	<10	25	<10	5	46
32	G36602	1.9	0.81	55	60	<5	2.39	2	10	66	192	2.27	10	0.14	1787	53	0.02	21	380	114	60	<20	152	0.03	<10	34	<10	4	73
33	G36603	2.3	0.19	20	60	15	1.68	1	4	53	86	1.65	<10	0.02	808	27	0.02	4	100	50	20	<20	125	0.01	60	11	<10	<1	23
34	G36604	1.5	0.21	15	55	<5	1.81	2	4	56	229	1.72	10	0.02	986	24	0.01	3	340	36	10	<20	135	0.02	<10	15	<10	2	140
35	G36605	2.0	0.34	30	55	<5	3.16	2	6	53	1263	2.05	10	0.09	2067	10	0.01	5	990	46	10	<20	210	0.03	<10	40	<10	5	65
QC DATA:																													
Repeat:																													
1	G36571	2.4	1.14	15	80	<5	2.90	2	16	76	672	3.58	20	0.91	1358	8	0.06	27	790	56	5	<20	182	0.05	<10	167	<10	6	77
10	G36580	1.6	0.83	<5	65	<5	2.64	1	11	60	512	2.80	20	0.62	2216	7	0.06	14	550	16	<5	<20	191	0.05	<10	92	<10	4	21
19	G36589	1.5	0.92	<5	65	<5	2.11	1	10	60	615	3.32	20	0.81	1991	12	0.05	13	390	30	<5	<20	181	0.05	<10	98	<10	2	36
Resplit:																													
1	G36571	2.4	1.13	10	70	<5	2.63	1	15	68	643	3.37	20	0.82	1212	9	0.05	27	790	58	10	<20	161	0.04	<10	176	<10	5	74
Standard:																													
Pb113		11.0	0.26	45	65	<5	1.70	40	2	5	2298	1.02	<10	0.12	1455	80	0.02	2	60	5402	15	<20	84	0.02	<10	8	<10	<1	6939

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5478
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5479

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07039
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34551	0.30	0.009
2	G34552	0.52	0.015
3	G34553	0.27	0.008
4	G34554	0.34	0.010
5	G34555	0.03	0.001
6	G34556	0.06	0.002
7	G34557	0.05	0.001
8	G34558	0.08	0.002
9	G34559	0.06	0.002
10	G34560	0.12	0.003
11	G34561	0.12	0.003
12	G34562	0.25	0.007
13	G34563	0.07	0.002
14	G34564	0.07	0.002
15	G34565	0.12	0.003
16	G34566	0.28	0.008
17	G34567	0.06	0.002
18	G34568	0.05	0.001
19	G34569	0.07	0.002
20	G34570	0.09	0.003
21	G34571	0.26	0.008
22	G34572	0.19	0.006
23	G34573	0.27	0.008
24	G34574	0.64	0.019
25	G34575	0.43	0.013
26	G34576	0.28	0.008
27	G34577	0.09	0.003

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

16-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5479

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07039
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34551	4.3	0.59	<5	55	<5	2.12	26	10	74	923	3.05	<10	0.35	694	57	0.02	5	940	202	<5	<20	83	0.05	<10	25	<10	5	1107
2	G34552	2.2	0.89	<5	180	<5	2.09	2	11	65	2303	3.04	<10	0.62	699	48	0.03	4	840	38	5	<20	121	0.07	<10	44	<10	6	75
3	G34553	1.0	0.82	<5	245	<5	2.50	<1	8	52	957	2.23	<10	0.56	660	76	0.03	3	1020	26	<5	<20	172	0.07	<10	28	<10	7	58
4	G34554	0.9	0.85	15	165	<5	3.02	<1	8	77	645	1.98	<10	0.50	859	36	0.02	3	930	28	<5	<20	105	0.05	<10	19	<10	7	48
5	G34555	<0.2	1.56	<5	255	<5	1.81	1	14	41	390	3.51	10	1.26	752	5	0.03	6	1280	32	10	<20	143	0.04	<10	90	<10	6	69
6	G34556	1.1	1.07	5	315	<5	2.49	1	13	81	1460	3.40	<10	0.81	758	6	0.08	8	1610	42	<5	<20	224	0.06	<10	535	<10	5	82
7	G34557	0.7	0.95	<5	480	<5	2.03	<1	7	67	914	3.22	<10	0.74	606	4	0.06	6	930	50	<5	<20	234	0.05	<10	626	<10	4	75
8	G34558	1.1	0.72	15	95	<5	1.37	<1	12	94	1304	2.92	<10	0.59	442	8	0.04	10	1120	24	<5	<20	155	0.03	<10	313	<10	4	48
9	G34559	0.7	0.60	65	160	<5	0.87	<1	7	71	860	1.88	<10	0.48	308	5	0.04	6	1100	20	<5	<20	104	0.02	<10	171	<10	5	39
10	G34560	1.5	0.77	140	100	<5	1.06	3	12	74	1896	2.95	<10	0.99	444	12	0.03	9	1700	20	10	<20	130	0.03	<10	172	<10	5	86
11	G34561	1.2	0.74	95	125	<5	1.33	3	10	75	1248	2.39	10	0.84	521	7	0.03	8	2080	28	15	<20	128	0.02	<10	233	<10	6	64
12	G34562	1.8	0.86	40	145	<5	1.58	29	13	62	1190	3.17	<10	0.85	776	10	0.04	7	1930	136	<5	<20	149	0.04	<10	416	<10	4	1135
13	G34563	1.0	1.20	5	525	<5	1.88	<1	10	65	1187	3.20	<10	1.10	831	5	0.06	7	1670	48	<5	<20	214	0.08	<10	628	<10	5	106
14	G34564	0.9	0.74	50	135	<5	2.05	2	13	59	1291	2.54	<10	0.80	928	7	0.04	9	2010	30	10	<20	154	0.04	<10	172	<10	7	67
15	G34565	1.0	0.92	75	145	<5	1.63	2	14	61	1276	2.41	10	0.86	805	8	0.05	9	1970	60	10	<20	102	0.03	<10	172	<10	6	73
16	G34566	3.1	1.26	30	55	<5	0.98	3	21	60	2637	3.50	20	0.66	196	211	0.04	10	440	60	10	<20	58	0.05	<10	48	<10	6	258
17	G34567	0.4	1.22	10	420	<5	2.24	<1	11	53	641	2.58	<10	1.10	861	5	0.07	8	1940	32	<5	<20	207	0.08	<10	285	<10	5	53
18	G34568	0.5	1.10	5	210	<5	1.83	<1	13	64	734	2.38	<10	0.94	757	4	0.08	8	1650	34	5	<20	146	0.08	<10	261	<10	5	52
19	G34569	0.6	1.66	10	265	<5	1.24	1	15	45	1338	3.57	<10	1.70	919	6	0.06	12	1930	46	10	<20	101	0.10	<10	401	<10	6	100
20	G34570	0.5	1.28	10	325	<5	2.06	<1	13	50	872	3.43	<10	1.26	951	4	0.06	10	1800	38	<5	<20	159	0.06	<10	347	<10	3	94
21	G34571	2.3	0.68	95	70	<5	2.24	2	14	55	1405	3.08	<10	0.45	1841	42	0.01	15	930	100	5	<20	146	0.03	<10	116	<10	5	109
22	G34572	2.3	1.07	20	75	<5	3.00	2	11	61	1104	2.82	20	0.64	1995	64	0.01	15	860	72	20	<20	179	0.03	<10	211	<10	5	82
23	G34573	2.4	1.18	20	105	<5	4.66	<1	7	64	1318	2.13	20	0.42	2237	13	0.01	7	1190	36	5	<20	236	0.05	<10	329	<10	7	53
24	G34574	3.9	1.00	30	90	<5	4.55	<1	11	52	1292	2.53	20	0.27	2036	7	<0.01	10	990	38	<5	<20	218	0.06	<10	307	<10	6	39
25	G34575	5.1	1.28	30	105	<5	4.60	1	11	54	1793	3.08	10	0.71	2393	14	<0.01	9	850	52	5	<20	214	0.08	<10	356	<10	4	57

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34576	2.5	1.20	30	100	<5	5.57	<1	11	62	1121	2.66	10	0.60	2883	9	0.01	8	870	52	5	<20	261	0.07	<10	270	<10	4	48
27	G34577	2.5	1.39	20	110	<5	5.10	<1	9	49	1547	2.58	10	1.00	2641	8	0.02	6	890	40	5	<20	252	0.09	<10	343	<10	5	53
28	G34578	4.4	1.68	35	130	<5	3.41	2	16	61	1955	3.86	20	1.50	2180	19	0.03	20	880	218	15	<20	185	0.11	<10	443	<10	6	122
29	G34579	3.7	0.59	25	80	<5	2.15	<1	11	82	1149	2.56	20	0.28	1198	36	0.02	12	590	70	<5	<20	139	0.05	<10	110	<10	4	30
30	G34580	<0.2	1.14	15	260	20	0.59	<1	7	65	6	2.27	<10	0.65	570	4	0.11	6	990	20	<5	<20	96	0.14	<10	50	<10	4	43
31	G34581	3.0	0.80	15	95	<5	3.02	1	14	55	1085	3.58	<10	0.51	1974	44	0.05	14	860	118	5	<20	351	0.04	<10	85	<10	6	63
32	G34582	2.5	0.54	20	60	<5	1.24	<1	13	129	2066	3.11	<10	0.41	613	59	0.01	8	740	20	<5	<20	143	0.01	<10	17	<10	5	34
33	G34583	3.6	0.82	20	55	<5	0.19	1	8	135	3322	3.57	<10	0.43	312	79	<0.01	8	590	30	15	<20	24	<0.01	<10	20	<10	2	58
34	G34584	3.4	0.85	15	55	<5	0.19	<1	8	148	3219	3.33	<10	0.44	317	59	<0.01	6	570	28	<5	<20	18	<0.01	<10	20	<10	2	56
35	G34585	2.4	0.89	30	70	<5	0.23	1	10	170	2000	3.93	<10	0.39	303	45	<0.01	7	790	34	<5	<20	21	0.01	<10	21	<10	3	54
QC DATA:																													
Repeat:																													
1	G34551	4.3	0.65	5	70	<5	2.16	27	11	78	930	3.09	<10	0.36	707	52	0.02	4	960	206	<5	<20	95	0.06	<10	26	<10	7	1116
10	G34560	1.5	0.82	140	105	<5	1.06	3	12	79	1911	3.01	<10	0.99	449	12	0.03	9	1720	22	10	<20	136	0.04	<10	181	<10	6	86
19	G34569	0.6	1.79	15	265	<5	1.30	<1	16	49	1404	3.72	<10	1.77	961	6	0.08	12	2020	52	10	<20	102	0.10	<10	432	<10	8	103
Resplit:																													
1	G34551	5.2	0.67	<5	60	<5	2.14	23	11	74	931	3.01	<10	0.34	751	49	0.02	5	1010	192	<5	<20	88	0.06	<10	27	<10	6	1224
Standard:																													
GEO'07		11.2	0.31	40	80	<5	1.75	38	3	7	2314	1.09	<10	0.12	1492	63	0.02	2	70	5460	15	<20	89	0.02	<10	9	<10	<1	6993

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
dl/5479
XLS/07

Seabridge Gold Inc.5479 17-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G34578	0.09	0.003
29	G34579	0.21	0.006
30	G34580	<0.03	<0.001
31	G34581	0.16	0.005
32	G34582	0.72	0.021
33	G34583	1.29	0.038
34	G34584	1.03	0.030
35	G34585	1.00	0.029

QC DATA:

Repeat:

1	G34551	0.27	0.008
2	G34552	0.42	0.012
10	G34560	0.13	0.004
19	G34569	0.05	0.001
32	G34582	0.70	0.020
33	G34583	1.38	0.040

Resplits:

1	G34551	0.28	0.008

Standard:

SI25		1.79	0.052

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5484

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07041
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36641	0.15	0.004
2	G36642	0.10	0.003
3	G36643	0.23	0.007
4	G36644	0.26	0.008
5	G36645	0.13	0.004
6	G36646	0.32	0.009
7	G36647	0.57	0.017
8	G36648	0.29	0.008
9	G36649	0.25	0.007
10	G36650	0.24	0.007
11	G36651	0.15	0.004
12	G36652	0.19	0.006
13	G36653	<0.03	<0.001
14	G36654	0.49	0.014
15	G36655	0.16	0.005
16	G36656	0.49	0.014
17	G36657	0.29	0.008
18	G36658	0.08	0.002
19	G36659	0.11	0.003
20	G36660	0.07	0.002
21	G36661	0.18	0.005
22	G36662	0.73	0.021
23	G36663	0.06	0.002
24	G36664	0.05	0.001
25	G36665	1.84	0.054
26	G36666	0.13	0.004
27	G36667	0.06	0.002
28	G36668	0.15	0.004

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 5484 17-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G36669	0.10	0.003
30	G36670	0.05	0.001
31	G36671	0.10	0.003
32	G36672	0.07	0.002
33	G36673	0.06	0.002
34	G36674	0.11	0.003
35	G36675	0.37	0.011

QC DATA:

Repeat:

1	G36641	0.14	0.004
10	G36650	0.21	0.006
19	G36659	0.11	0.003

Resplits:

1	G36641	0.13	0.004

Standard:

Si25		1.78	0.052

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

1 ‘g-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5484

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07041
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36641	2.6	1.00	30	80	<5	4.03	<1	10	47	1211	2.49	20	0.59	2149	4	0.03	5	1110	38	5	<20	219	0.04	<10	175	<10	5	27
2	G36642	1.3	0.75	25	105	<5	2.84	<1	6	54	623	1.40	20	0.36	1605	3	0.03	4	1160	30	<5	<20	153	0.03	<10	94	<10	4	21
3	G36643	2.2	0.96	15	85	<5	3.52	<1	9	41	1232	2.39	10	0.55	2159	9	0.03	5	950	36	<5	<20	187	0.04	<10	175	<10	6	43
4	G36644	1.3	0.74	105	70	<5	2.04	2	13	59	967	3.02	<10	0.42	1447	12	0.02	12	1000	200	10	<20	86	0.02	<10	114	<10	6	64
5	G36645	1.0	0.39	<5	120	<5	2.39	1	13	58	1757	3.00	10	0.70	1302	16	0.05	16	1000	34	5	<20	73	0.02	<10	124	<10	5	63
6	G36646	1.6	0.28	20	60	<5	3.50	1	17	66	2342	3.99	<10	0.75	1449	58	0.04	15	680	24	5	<20	123	0.02	<10	131	<10	5	50
7	G36647	2.5	0.39	15	75	<5	2.46	<1	17	55	3616	4.05	<10	0.45	1476	9	0.02	16	1020	48	<5	<20	84	0.02	<10	151	<10	8	79
8	G36648	2.5	0.38	10	110	<5	1.81	3	11	37	1067	3.24	10	0.37	1444	11	0.03	20	1570	22	30	<20	63	<0.01	<10	63	<10	8	60
9	G36649	0.4	0.57	10	65	<5	4.03	<1	15	37	772	4.41	<10	0.95	1875	9	0.02	12	1130	54	<5	<20	180	0.03	<10	107	<10	6	78
10	G36650	0.7	0.51	<5	75	<5	2.65	<1	18	63	1709	4.19	<10	0.86	1374	13	0.02	11	990	38	<5	<20	106	0.03	<10	215	<10	4	64
11	G36651	0.5	0.28	<5	125	<5	2.71	<1	13	55	1563	3.23	<10	0.67	1226	9	0.03	7	980	110	<5	<20	116	0.02	<10	100	<10	4	46
12	G36652	0.4	0.33	<5	75	<5	1.94	1	16	61	1347	3.54	10	0.56	1140	8	0.03	8	1070	34	<5	<20	76	0.02	<10	193	<10	3	53
13	G36653	<0.2	1.10	20	270	15	0.70	<1	7	91	7	2.08	<10	0.64	569	2	0.13	7	950	28	5	<20	114	0.13	<10	50	<10	4	44
14	G36654	1.7	0.44	10	70	<5	2.19	1	20	61	4360	3.77	<10	0.76	1259	13	0.02	11	990	56	<5	<20	78	0.02	<10	205	<10	6	43
15	G36655	0.7	0.65	25	70	<5	2.53	<1	16	58	1252	3.91	<10	0.92	1379	43	0.04	42	1230	50	<5	<20	81	0.03	<10	124	<10	7	49
16	G36656	1.8	1.12	65	75	<5	5.30	<1	17	65	1334	3.52	<10	1.42	2286	10	0.03	35	1080	42	10	<20	240	0.06	<10	154	<10	9	44
17	G36657	0.8	1.44	20	100	<5	5.01	<1	15	77	1121	4.41	<10	1.71	2160	46	0.04	53	1400	40	10	<20	253	0.08	<10	273	<10	8	63
18	G36658	0.4	1.62	30	120	<5	4.80	<1	13	81	566	3.97	<10	2.15	2083	17	0.13	67	1260	36	15	<20	286	0.13	<10	231	<10	8	74
19	G36659	0.5	1.55	25	110	<5	4.32	<1	14	76	902	4.11	<10	1.84	1765	25	0.12	56	1150	40	10	<20	278	0.12	<10	275	<10	6	62
20	G36660	0.7	1.81	30	125	<5	3.51	<1	15	63	753	4.58	<10	2.27	1514	11	0.12	36	1060	62	15	<20	245	0.14	<10	302	<10	5	74
21	G36661	2.3	1.83	35	95	<5	5.06	<1	29	63	2377	5.89	<10	2.62	2205	20	0.02	38	830	96	15	<20	283	0.09	<10	275	<10	6	64
22	G36662	0.9	1.69	25	100	<5	3.81	<1	29	63	1534	7.34	<10	2.06	2122	22	0.06	23	820	52	10	<20	264	0.11	<10	342	<10	2	74
23	G36663	0.5	1.49	25	100	<5	5.68	<1	23	55	820	5.91	<10	1.34	2198	9	0.03	24	870	62	5	<20	393	0.09	<10	283	<10	4	61
24	G36664	0.5	1.59	35	130	<5	2.68	<1	16	75	509	4.58	<10	1.84	1085	11	0.22	23	1080	80	10	<20	274	0.11	<10	271	<10	6	57
25	G36665	3.9	1.05	50	45	<5	1.11	2	24	54	8546	4.17	20	0.66	219	608	0.05	64	80	74	25	<20	53	0.03	<10	49	<10	5	80

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36666	0.8	1.78	5	130	<5	3.74	1	41	66	1252	8.63	<10	2.28	1485	11	0.13	37	1230	64	<5	<20	347	0.14	<10	367	<10	<1	82
27	G36667	0.8	2.27	30	165	<5	2.67	<1	38	70	863	7.16	<10	2.79	1190	8	0.17	49	1200	78	10	<20	235	0.19	<10	239	<10	3	89
28	G36668	1.1	2.22	45	140	<5	2.37	1	28	92	972	5.96	<10	2.74	1139	15	0.17	51	1180	118	20	<20	216	0.16	<10	314	<10	3	112
29	G36669	0.6	2.36	25	170	<5	3.52	2	39	74	971	7.86	<10	3.14	1605	13	0.11	58	1220	66	30	<20	357	0.17	<10	294	<10	3	106
30	G36670	0.9	2.12	30	120	<5	1.81	<1	25	73	755	5.39	<10	2.55	960	14	0.18	36	1110	118	15	<20	177	0.15	<10	199	<10	3	83
31	G36671	1.0	2.10	40	165	<5	3.11	<1	31	82	1179	5.95	<10	2.59	1406	8	0.21	55	1090	68	15	<20	292	0.17	<10	294	<10	5	77
32	G36672	0.3	2.26	15	150	<5	2.98	<1	25	65	813	6.81	<10	3.64	1695	11	0.16	23	830	66	15	<20	237	0.13	<10	307	<10	2	96
33	G36673	0.3	1.18	30	95	<5	2.52	<1	13	83	721	3.92	<10	1.06	843	8	0.24	17	640	36	10	<20	205	0.06	<10	231	<10	2	40
34	G36674	0.8	1.33	30	105	<5	3.33	<1	34	79	1342	5.38	<10	1.21	1174	20	0.14	21	740	40	<5	<20	271	0.06	<10	254	<10	3	56
35	G36675	1.5	1.30	<5	100	<5	2.13	2	80	68	2188	>10	<10	1.39	1643	11	0.06	20	640	44	<5	<20	226	0.10	<10	450	<10	<1	64
QC DATA:																													
Repeat:																													
1	G36641	2.7	0.94	30	80	<5	3.98	<1	9	46	1200	2.45	20	0.58	2127	3	0.03	6	1090	36	5	<20	216	0.04	<10	164	<10	5	27
10	G36650	0.7	0.50	15	75	<5	2.70	2	19	63	1707	4.24	10	0.88	1394	13	0.02	13	1030	40	15	<20	107	0.02	<10	211	<10	5	66
19	G36659	0.5	1.54	35	105	<5	4.39	<1	14	76	900	4.19	<10	1.83	1789	27	0.12	59	1180	40	15	<20	270	0.11	<10	271	<10	5	64
Resplit:																													
1	G36641	2.4	1.00	35	90	<5	4.09	<1	10	48	1138	2.60	20	0.58	2155	3	0.03	5	1180	36	10	<20	224	0.04	<10	184	<10	5	30
Standard:																													
Pb113		11.0	0.30	40	75	<5	1.84	37	3	7	2272	1.14	<10	0.12	1553	68	0.02	4	110	5526	20	<20	85	0.02	<10	10	<10	<1	6912

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
dl/5479
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5485

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07042
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34621	0.73	0.021
2	G34622	0.80	0.023
3	G34623	0.78	0.023
4	G34624	0.68	0.020
5	G34625	0.78	0.023
6	G34626	0.45	0.013
7	G34627	0.40	0.012
8	G34628	0.56	0.016
9	G34629	0.74	0.022
10	G34630	0.75	0.022
11	G34631	0.81	0.024
12	G34632	0.67	0.020
13	G34633	0.92	0.027
14	G34634	0.92	0.027
15	G34635	1.36	0.040
16	G34636	0.64	0.019
17	G34637	0.69	0.020
18	G34638	0.83	0.024
19	G34639	0.84	0.024
20	G34640	<0.03	<0.001
21	G34641	1.86	0.054
22	G34642	0.75	0.022
23	G34643	0.61	0.018
24	G34644	0.77	0.022
25	G34645	0.73	0.021
26	G34646	0.58	0.017
27	G34647	0.44	0.013
28	G34648	0.55	0.016

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 17-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G34649	0.58	0.017
30	G34650	0.61	0.018
31	G34651	0.77	0.022
32	G34652	0.79	0.023
33	G34653	0.48	0.014
34	G34654	0.57	0.017
35	G34655	0.76	0.022

QC DATA:

Repeat:

1	G34621	0.73	0.021
10	G34630	0.73	0.021
19	G34639	0.77	0.022

Resplits:

1	G34621	0.59	0.017

Standard:

Si25		1.79	0.052

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

1 'g-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5485

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07042
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34621	2.3	0.77	<5	90	<5	1.21	<1	10	116	1745	2.79	<10	0.44	597	38	0.02	5	590	32	<5	<20	89	0.02	<10	21	<10	4	49
2	G34622	2.8	0.66	<5	95	<5	1.09	1	8	105	2619	2.43	<10	0.39	497	23	0.02	5	460	28	10	<20	57	0.01	<10	21	<10	4	45
3	G34623	2.8	0.34	<5	55	<5	0.87	2	14	149	2303	2.86	<10	0.11	337	37	0.01	6	400	30	<5	<20	45	0.01	<10	13	<10	1	31
4	G34624	3.6	0.48	<5	55	<5	0.79	2	12	157	2934	2.84	<10	0.25	384	32	0.01	6	440	44	<5	<20	60	0.01	<10	18	<10	2	42
5	G34625	2.1	0.69	<5	60	<5	1.43	1	9	116	1672	3.35	<10	0.43	567	43	0.02	6	650	28	<5	<20	113	0.02	<10	29	<10	3	55
6	G34626	1.8	0.76	<5	75	<5	1.73	<1	9	129	1431	3.37	<10	0.47	670	28	0.02	6	700	28	<5	<20	148	0.03	<10	30	<10	5	58
7	G34627	2.0	0.66	<5	90	<5	0.69	<1	7	126	1847	3.32	<10	0.44	396	48	0.02	5	530	20	<5	<20	53	0.02	<10	37	<10	2	45
8	G34628	1.8	0.65	<5	65	<5	0.65	<1	10	145	1708	2.99	<10	0.44	365	31	0.03	5	620	24	<5	<20	51	0.02	<10	34	<10	2	45
9	G34629	2.1	0.64	<5	60	<5	0.56	2	11	133	1850	3.15	<10	0.43	387	81	0.02	7	460	26	15	<20	46	<0.01	<10	30	<10	1	44
10	G34630	2.1	0.71	<5	65	<5	0.69	<1	11	121	1918	3.36	<10	0.45	446	77	0.01	5	520	26	<5	<20	59	0.02	<10	34	<10	2	52
11	G34631	3.1	0.52	20	45	<5	0.31	9	10	119	2242	3.77	<10	0.27	226	94	<0.01	6	710	164	<5	<20	23	0.01	<10	17	<10	2	261
12	G34632	2.0	0.88	15	55	<5	0.42	<1	10	143	1891	3.48	<10	0.58	451	37	0.01	6	770	34	5	<20	40	0.01	<10	30	<10	3	77
13	G34633	2.5	0.71	20	50	<5	0.29	1	11	132	2138	3.52	<10	0.47	335	88	0.02	7	600	28	<5	<20	28	0.01	<10	29	<10	2	64
14	G34634	2.9	0.71	5	40	<5	0.26	1	9	135	2573	3.05	<10	0.48	303	47	0.02	6	670	22	<5	<20	8	<0.01	<10	26	<10	<1	61
15	G34635	4.2	0.62	<5	55	<5	0.65	1	9	121	4077	2.81	<10	0.38	381	136	0.02	5	550	28	<5	<20	58	<0.01	<10	23	<10	3	56
16	G34636	1.7	1.25	<5	110	<5	1.74	3	11	97	1712	3.76	<10	0.91	981	51	0.01	6	1100	40	5	<20	130	0.02	<10	35	<10	4	182
17	G34637	1.8	0.92	<5	125	<5	1.78	2	11	101	1756	3.73	<10	0.60	816	83	0.02	5	880	30	5	<20	144	0.02	<10	44	<10	3	132
18	G34638	2.2	0.88	<5	95	<5	1.58	2	10	87	2451	3.28	<10	0.65	743	59	0.03	5	820	30	5	<20	147	0.02	<10	44	<10	4	135
19	G34639	1.9	1.01	<5	115	<5	1.45	3	10	99	2121	3.68	<10	0.71	877	109	0.02	8	890	36	20	<20	133	0.02	<10	40	<10	4	135
20	G34640	<0.2	1.05	5	265	10	0.59	<1	7	87	7	2.20	<10	0.62	529	3	0.11	6	910	20	<5	<20	93	0.12	<10	48	<10	2	44
21	G34641	4.0	1.17	30	50	<5	1.04	2	23	61	8508	4.16	10	0.64	210	615	0.05	64	130	72	25	<20	63	0.02	<10	45	<10	6	73
22	G34642	1.8	1.04	<5	135	<5	1.35	2	11	94	1861	3.15	<10	0.72	727	60	0.02	6	980	32	10	<20	120	0.01	<10	32	<10	4	115
23	G34643	3.3	0.76	10	65	<5	1.12	2	11	138	2818	3.21	<10	0.45	607	66	0.01	6	750	32	<5	<20	68	<0.01	<10	17	<10	3	99
24	G34644	3.0	0.87	40	60	<5	1.11	4	13	140	1646	3.64	<10	0.54	650	51	<0.01	7	1030	44	5	<20	76	0.02	<10	18	<10	4	206
25	G34645	2.9	1.00	25	65	<5	0.78	4	11	120	2250	3.88	<10	0.75	682	72	0.01	7	920	180	<5	<20	50	0.01	<10	25	<10	4	279

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34646	1.6	1.09	<5	80	<5	1.47	6	13	92	1506	3.76	<10	0.75	877	34	0.01	6	1140	56	5	<20	122	0.02	<10	29	<10	3	232
27	G34647	1.2	1.11	<5	140	<5	1.05	3	11	82	1340	4.17	<10	0.77	787	53	0.02	6	1240	60	5	<20	88	0.02	<10	51	<10	3	174
28	G34648	1.4	1.06	<5	120	<5	1.27	2	11	94	1540	3.87	<10	0.78	775	63	0.03	6	1010	38	5	<20	143	0.02	<10	51	<10	4	174
29	G34649	1.7	0.98	<5	100	<5	0.66	1	12	101	1584	3.64	<10	0.70	528	85	0.02	5	940	36	<5	<20	60	0.02	<10	44	<10	2	103
30	G34650	1.8	1.09	<5	90	<5	0.75	3	11	82	1979	4.03	<10	0.82	629	79	0.02	8	1050	40	15	<20	71	0.01	<10	54	<10	4	142
31	G34651	2.5	0.86	15	80	<5	1.37	2	11	105	2119	3.09	<10	0.54	721	196	0.01	4	840	34	5	<20	122	0.02	<10	26	<10	4	142
32	G34652	2.4	0.94	<5	90	<5	1.40	5	12	115	2114	3.49	<10	0.68	732	97	0.02	6	740	36	<5	<20	138	0.02	<10	45	<10	3	260
33	G34653	1.2	1.20	<5	145	<5	1.92	6	11	85	1178	4.08	<10	0.95	976	60	0.05	6	1090	38	10	<20	186	0.03	<10	71	<10	3	271
34	G34654	2.0	1.10	<5	65	<5	1.44	6	11	99	1598	3.94	<10	0.84	853	80	0.03	6	1080	32	10	<20	120	0.02	<10	53	<10	3	236
35	G34655	18.0	0.36	35	40	<5	1.05	1	9	124	4289	2.69	<10	0.12	373	1132	0.01	4	590	38	<5	<20	77	<0.01	<10	10	<10	4	50
QC DATA:																													
Repeat:																													
1	G34621	2.2	0.74	10	80	<5	1.23	<1	11	114	1770	2.83	<10	0.45	605	38	0.02	5	610	34	<5	<20	94	0.02	<10	20	<10	4	50
10	G34630	2.2	0.70	<5	65	<5	0.70	1	11	118	1955	3.40	<10	0.46	453	80	0.02	6	540	26	<5	<20	63	0.02	<10	33	<10	2	53
19	G34639	1.9	0.99	<5	105	<5	1.46	2	10	98	2117	3.67	<10	0.70	880	99	0.02	5	880	34	5	<20	132	0.02	<10	38	<10	4	137
Resplit:																													
1	G34621	1.8	0.81	10	90	<5	1.27	<1	8	119	1733	2.96	<10	0.48	862	37	0.02	6	650	34	5	<20	145	0.02	<10	23	<10	5	51
Standard:																													
Pb113		11.4	0.27	50	70	<5	1.70	36	2	6	2193	1.06	<10	0.11	1468	83	0.02	3	80	5414	25	<20	88	0.01	<10	8	<10	<1	6995

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
dl/1107
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5487

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07038
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36606	0.33	0.010
2	G36607	0.16	0.005
3	G36608	0.33	0.010
4	G36609	0.09	0.003
5	G36610	0.55	0.016
6	G36611	0.41	0.012
7	G36612	0.14	0.004
8	G36613	0.08	0.002
9	G36614	0.44	0.013
10	G36615	0.10	0.003
11	G36616	0.97	0.028
12	G36617	0.08	0.002
13	G36618	0.10	0.003
14	G36619	0.18	0.005
15	G36620	0.21	0.006
16	G36621	0.34	0.010
17	G36622	0.15	0.004
18	G36623	0.10	0.003
19	G36624	<0.03	<0.001
20	G36625	0.12	0.003
21	G36626	0.34	0.010
22	G36627	0.22	0.006
23	G36628	0.20	0.006
24	G36629	0.18	0.005
25	G36630	0.26	0.008
26	G36631	0.44	0.013
27	G36632	0.20	0.006
28	G36633	0.34	0.010

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 5487 17-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G36634	0.26	0.008
30	G36635	0.22	0.006
31	G36636	0.11	0.003
32	G36637	0.12	0.003
33	G36638	0.07	0.002
34	G36639	0.23	0.007
35	G36640	0.08	0.002

QC DATA:

Repeat:

1	G36606	0.30	0.009
5	G36610	0.53	0.015
10	G36615	0.09	0.003
15	G36620	0.22	0.006
20	G36625	0.13	0.004
31	G36636	0.09	0.003
32	G36637	0.11	0.003

Resplits:

1	G36606	0.29	0.008

Standard:

Si25		1.79	0.052

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

16-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5487

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07038
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36606	2.6	0.53	25	60	60	3.19	1	13	60	630	3.92	<10	0.24	2561	43	0.01	8	870	82	<5	<20	218	0.04	<10	74	<10	4	75
2	G36607	6.4	0.67	150	55	<5	3.39	2	12	57	4777	4.41	20	0.21	2184	46	0.01	7	560	110	145	<20	208	0.02	<10	143	<10	4	120
3	G36608	3.4	0.34	50	50	<5	3.28	2	9	92	1843	3.11	<10	0.06	1612	24	0.01	8	810	68	20	<20	224	0.01	<10	50	<10	4	166
4	G36609	0.5	0.23	25	40	<5	1.62	<1	3	64	72	1.15	<10	0.03	724	5	<0.01	3	80	16	<5	<20	131	0.01	<10	13	<10	1	15
5	G36610	1.3	0.27	25	45	<5	3.01	<1	4	59	229	1.47	<10	0.12	1457	5	0.01	5	80	14	10	<20	194	<0.01	<10	31	<10	2	9
6	G36611	2.4	0.18	25	55	<5	2.62	<1	6	75	390	1.94	<10	0.03	1099	6	0.01	5	90	20	5	<20	191	0.01	<10	20	<10	2	15
7	G36612	1.1	0.20	20	45	<5	2.31	<1	4	59	213	1.51	<10	0.03	967	5	0.01	5	170	16	<5	<20	193	0.01	<10	18	<10	2	2
8	G36613	0.4	0.22	15	50	<5	1.91	<1	3	71	71	1.24	<10	0.03	837	6	0.01	3	110	14	<5	<20	166	0.01	<10	21	<10	2	2
9	G36614	1.9	0.28	45	50	5	2.87	<1	5	69	91	2.61	<10	0.08	1362	4	0.01	5	110	28	<5	<20	184	0.02	<10	47	<10	<1	13
10	G36615	0.7	0.23	20	55	<5	2.66	<1	4	57	58	1.94	<10	0.06	1108	4	0.01	2	50	24	<5	<20	177	0.02	<10	37	<10	<1	24
11	G36616	3.6	1.12	60	70	<5	0.73	3	17	58	3282	3.90	20	0.51	274	213	0.03	15	310	132	35	<20	35	0.03	<10	44	<10	5	151
12	G36617	0.7	0.19	25	50	<5	2.47	<1	3	58	116	1.25	<10	0.03	1005	4	0.01	2	60	20	<5	<20	186	0.01	<10	19	<10	<1	17
13	G36618	1.0	0.32	20	55	<5	2.54	<1	5	62	50	1.91	<10	0.13	1100	5	0.01	4	100	30	<5	<20	182	0.02	<10	46	<10	<1	21
14	G36619	1.6	0.48	30	50	<5	3.12	<1	6	63	118	2.33	<10	0.32	1490	5	0.01	4	100	30	<5	<20	213	0.03	<10	83	<10	2	23
15	G36620	3.6	0.64	35	45	<5	4.77	<1	12	53	1089	3.10	<10	0.36	2485	7	0.01	12	500	68	5	<20	280	0.03	<10	224	<10	3	86
16	G36621	2.2	0.74	30	65	<5	4.59	2	11	54	240	3.58	<10	0.42	2407	10	0.01	13	340	44	15	<20	285	0.03	<10	364	<10	3	33
17	G36622	1.3	0.40	25	60	<5	1.97	<1	4	58	241	1.77	<10	0.20	1215	4	0.01	4	100	28	5	<20	140	0.02	<10	63	<10	<1	14
18	G36623	0.7	0.36	25	50	<5	1.73	<1	4	53	130	1.48	<10	0.16	1039	5	0.01	3	160	20	<5	<20	125	0.01	<10	57	<10	1	11
19	G36624	<0.2	1.06	10	265	5	0.61	<1	7	100	4	2.31	<10	0.64	578	4	0.11	8	930	24	5	<20	91	0.10	<10	50	<10	2	45
20	G36625	1.0	0.32	40	40	<5	1.55	<1	5	58	180	1.81	<10	0.11	874	13	0.02	3	150	26	<5	<20	105	0.02	<10	30	<10	1	8
21	G36626	0.8	0.58	60	55	<5	2.66	<1	5	50	675	1.91	<10	0.44	1757	9	0.01	5	140	38	10	<20	179	0.02	<10	111	<10	2	20
22	G36627	1.6	0.29	30	45	<5	2.27	<1	3	42	558	1.31	10	0.08	1132	5	0.01	3	120	22	5	<20	143	0.01	<10	50	<10	2	7
23	G36628	1.7	0.30	40	40	<5	2.50	<1	5	49	549	1.51	10	0.05	1156	6	0.02	3	100	16	5	<20	172	0.01	<10	56	<10	2	5
24	G36629	1.1	0.20	25	30	<5	3.04	<1	4	54	408	1.60	<10	0.02	1396	8	0.03	2	80	16	<5	<20	186	0.02	<10	22	<10	<1	6
25	G36630	1.8	1.02	50	70	<5	4.46	<1	11	43	169	3.08	<10	0.50	2681	8	0.01	11	360	38	5	<20	211	0.04	<10	136	<10	3	30

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36631	2.7	0.82	45	65	<5	3.82	<1	9	51	681	3.33	10	0.34	2853	10	0.01	8	560	42	<5	<20	188	0.04	<10	201	<10	4	47
27	G36632	3.3	0.87	45	75	<5	3.39	2	12	56	1203	3.59	20	0.48	2582	17	0.01	11	720	48	15	<20	146	0.03	<10	318	<10	3	45
28	G36633	8.5	0.79	45	70	<5	2.83	1	13	51	3120	4.93	10	0.48	2225	26	0.01	10	660	48	5	<20	131	0.03	<10	326	<10	3	40
29	G36634	3.1	0.45	60	55	<5	2.66	<1	10	56	679	3.73	<10	0.17	1437	10	0.02	6	130	32	<5	<20	139	0.02	<10	134	<10	<1	20
30	G36635	2.4	0.34	25	50	15	2.54	1	9	61	308	5.64	<10	0.09	1548	11	0.04	5	40	40	<5	<20	150	0.03	<10	47	<10	<1	20
31	G36636	3.2	0.30	20	55	<5	2.89	<1	6	53	1024	1.77	10	0.05	1156	4	0.03	4	640	32	<5	<20	133	0.01	<10	58	<10	4	26
32	G36637	3.7	0.77	35	80	<5	3.98	<1	11	50	1828	2.70	10	0.33	1840	5	0.02	7	730	46	10	<20	165	0.02	<10	156	<10	4	45
33	G36638	3.9	0.84	25	95	<5	5.46	<1	12	41	2078	3.35	<10	0.67	2502	5	0.02	7	630	46	<5	<20	252	0.04	<10	560	<10	3	55
34	G36639	2.4	1.14	30	95	<5	3.36	<1	9	50	1121	2.69	20	0.69	2334	7	0.02	8	970	40	10	<20	175	0.03	<10	237	<10	4	33
35	G36640	2.5	0.88	30	105	<5	4.32	<1	8	43	1212	2.20	10	0.54	2434	3	0.03	5	990	28	10	<20	240	0.03	<10	189	<10	4	25
QC DATA:																													
Repeat:																													
1	G36606	2.6	0.60	35	60	65	3.26	<1	13	65	640	3.94	<10	0.26	2604	43	0.01	7	870	84	5	<20	224	0.03	<10	84	<10	4	76
10	G36615	0.7	0.26	25	60	<5	2.68	<1	5	60	58	1.96	<10	0.07	1117	4	0.01	2	50	24	<5	<20	180	0.02	<10	43	<10	<1	24
19	G36624	<0.2	1.06	20	265	20	0.63	<1	8	103	6	2.30	<10	0.62	574	5	0.11	8	910	24	10	<20	100	0.10	<10	51	<10	3	45
Resplit:																													
1	G36606	2.3	0.60	20	65	<5	3.10	<1	13	56	686	4.23	<10	0.24	2415	47	0.01	8	950	76	<5	<20	203	0.03	<10	85	<10	4	73
Standard:																													
Pb113		11.6	0.30	45	75	<5	1.74	37	2	6	2276	1.10	<10	0.12	1504	87	0.02	4	90	5346	20	<20	80	<0.01	10	11	<10	<1	6940

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/1107
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5488

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07040
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34586	0.79	0.023
2	G34587	1.45	0.042
3	G34588	0.80	0.023
4	G34589	0.33	0.010
5	G34590	<0.03	<0.001
6	G34591	0.56	0.016
7	G34592	0.13	0.004
8	G34593	1.41	0.041
9	G34594	1.04	0.030
10	G34586	0.96	0.028
11	G34596	0.90	0.026
12	G34597	0.83	0.024
13	G34598	0.88	0.026
14	G34599	0.86	0.025
15	G34600	0.99	0.029
16	G34601	0.63	0.018
17	G34602	0.49	0.014
18	G34603	0.78	0.023
19	G34604	0.86	0.025
20	G34605	0.50	0.015
21	G34606	0.37	0.011
22	G34607	0.47	0.014
23	G34608	0.38	0.011
24	G34609	0.33	0.010
25	G34610	0.55	0.016
26	G34611	0.38	0.011
27	G34612	0.69	0.020
28	G34613	0.41	0.012

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5488 17-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G34614	0.62	0.018
30	G34615	0.42	0.012
31	G34616	0.62	0.018
32	G34617	1.06	0.031
33	G34618	1.05	0.031
34	G34619	0.61	0.018
35	G34620	0.61	0.018

QC DATA:

Repeat:

1	G34586	0.78	0.023
2	G34587	1.50	0.044
8	G34593	1.31	0.038
9	G34594	1.08	0.031
10	G34586	0.92	0.027
19	G34604	0.88	0.026
32	G34617	1.01	0.029
33	G34618	1.10	0.032

Resplits:

1	G34586	0.65	0.019

Standard:

SI25		1.79	0.052
SI25		1.80	0.052

AU: 30g FA/AA-Finish

JJ/nl/jl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

17-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5488

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07040
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34586	3.4	0.40	30	35	<5	0.16	3	6	162	2536	3.25	<10	0.12	116	40	<0.01	6	750	38	<5	<20	17	<0.01	<10	11	<10	<1	34
2	G34587	3.7	0.57	35	45	<5	0.25	2	10	117	3182	4.61	<10	0.22	191	27	<0.01	7	950	40	<5	<20	17	0.01	<10	21	<10	<1	50
3	G34588	2.8	0.72	30	50	<5	0.44	3	9	133	2644	3.67	<10	0.32	298	129	<0.01	7	1020	48	5	<20	26	<0.01	<10	15	<10	2	80
4	G34589	1.3	1.04	20	100	<5	0.64	1	12	111	1519	3.23	<10	0.53	468	46	<0.01	6	1060	42	10	<20	35	0.02	<10	17	<10	3	88
5	G34590	<0.2	1.08	25	275	10	0.62	<1	7	109	5	2.08	<10	0.65	573	4	0.10	7	990	20	5	<20	86	0.15	<10	49	<10	<1	48
6	G34591	1.8	1.21	25	85	<5	0.29	<1	10	107	1921	3.80	<10	0.61	372	37	<0.01	4	1070	44	<5	<20	12	0.02	<10	16	<10	2	110
7	G34592	0.9	2.47	50	110	<5	1.74	4	33	98	540	4.40	<10	2.35	876	16	<0.01	68	940	72	25	<20	163	0.03	<10	43	<10	4	175
8	G34593	5.1	1.23	40	50	<5	0.54	10	22	145	3041	5.07	<10	0.95	416	59	<0.01	37	560	66	10	<20	30	0.02	<10	24	<10	<1	290
9	G34594	10.2	0.54	45	45	<5	0.44	5	13	109	3710	5.22	<10	0.16	366	73	<0.01	8	1060	78	<5	<20	22	0.01	<10	10	<10	3	153
10	G34586	10.2	0.94	30	75	<5	1.46	5	7	126	2822	3.33	<10	0.43	861	32	<0.01	5	870	72	<5	<20	63	0.02	<10	16	<10	3	188
11	G34596	5.9	1.05	25	65	<5	1.12	3	9	123	3034	3.60	<10	0.54	690	20	<0.01	6	950	58	<5	<20	42	0.01	<10	15	<10	2	127
12	G34597	2.9	1.06	25	100	<5	1.10	2	9	143	2795	3.33	<10	0.47	577	38	<0.01	5	760	42	5	<20	47	0.01	<10	18	<10	2	102
13	G34598	2.8	1.12	15	105	<5	1.42	<1	8	109	3214	3.60	<10	0.56	647	35	<0.01	5	680	34	<5	<20	65	0.02	<10	19	<10	2	72
14	G34599	3.7	0.56	20	50	<5	1.69	<1	8	136	3620	2.63	<10	0.25	628	119	<0.01	6	650	34	<5	<20	86	<0.01	<10	10	<10	2	34
15	G34600	3.5	1.20	60	75	<5	0.73	6	18	53	3384	3.78	20	0.60	279	223	0.04	15	320	140	45	<20	32	0.04	<10	40	<10	6	152
16	G34601	2.3	0.59	25	80	<5	1.19	1	6	119	2171	1.81	<10	0.26	528	21	<0.01	5	630	36	<5	<20	52	<0.01	<10	9	<10	2	47
17	G34602	1.8	0.79	20	105	<5	1.62	1	6	110	1879	2.08	<10	0.43	781	35	0.01	5	770	28	5	<20	75	0.01	<10	16	<10	3	58
18	G34603	1.9	0.58	20	95	<5	1.37	<1	5	104	1946	1.73	<10	0.25	553	22	0.01	4	680	30	<5	<20	64	0.01	<10	8	<10	3	45
19	G34604	2.1	0.51	30	80	<5	1.90	2	6	89	2629	1.80	<10	0.19	668	40	<0.01	4	720	28	5	<20	63	<0.01	<10	7	<10	3	48
20	G34605	1.3	0.41	25	90	<5	2.18	1	6	98	1417	1.74	<10	0.15	547	19	0.02	6	800	22	10	<20	226	0.01	<10	10	<10	3	36
21	G34606	1.3	0.47	20	80	<5	1.86	<1	6	109	1100	1.58	<10	0.19	567	23	0.02	3	870	24	<5	<20	118	0.04	<10	9	<10	3	36
22	G34607	1.5	0.60	20	80	<5	1.84	2	10	95	1536	2.44	<10	0.36	627	57	0.02	5	1060	28	5	<20	93	0.05	<10	19	<10	5	47
23	G34608	1.2	0.73	25	125	<5	1.92	1	9	79	947	3.14	<10	0.48	676	24	0.02	4	1340	26	5	<20	97	0.08	<10	28	<10	5	61
24	G34609	1.2	0.72	15	120	<5	2.02	1	8	84	1029	3.10	<10	0.48	685	20	0.03	4	1260	28	<5	<20	89	0.07	<10	31	<10	4	64
25	G34610	1.8	0.65	20	45	<5	2.08	2	12	109	1445	3.61	<10	0.41	684	29	0.02	5	900	34	<5	<20	68	0.03	<10	22	<10	1	52

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34611	1.5	1.02	15	70	<5	1.29	2	9	112	1161	3.83	<10	0.65	567	48	0.01	5	1130	30	5	<20	70	0.02	<10	27	<10	3	57
27	G34612	2.4	0.88	20	70	<5	0.68	<1	7	123	1722	3.24	<10	0.58	388	35	0.01	6	920	30	5	<20	36	0.02	<10	24	<10	2	48
28	G34613	1.8	0.74	25	65	<5	1.01	2	8	131	1531	3.31	<10	0.40	448	40	<0.01	6	1070	38	<5	<20	60	0.02	<10	14	<10	5	41
29	G34614	2.1	0.65	20	50	<5	1.44	2	11	115	1796	3.84	<10	0.35	437	38	0.01	6	980	28	<5	<20	98	0.02	<10	17	<10	3	37
30	G34615	1.6	0.97	20	60	<5	0.91	2	9	119	1290	3.46	<10	0.65	580	70	<0.01	6	1050	26	<5	<20	49	0.03	<10	17	<10	2	76
31	G34616	2.5	0.94	20	65	<5	0.92	2	7	109	1987	3.05	<10	0.67	588	37	<0.01	7	900	30	15	<20	53	0.01	<10	17	<10	3	83
32	G34617	3.0	0.96	15	45	<5	1.08	2	8	118	2437	3.29	<10	0.65	590	101	0.01	6	1060	166	5	<20	64	0.03	<10	19	<10	4	62
33	G34618	3.6	0.81	15	85	<5	1.30	1	8	137	3129	2.82	<10	0.54	590	55	0.03	6	690	38	<5	<20	100	0.02	<10	29	<10	3	58
34	G34619	2.3	0.84	15	75	<5	1.22	2	8	109	1967	3.22	<10	0.50	683	43	0.01	3	890	34	<5	<20	83	0.02	<10	21	<10	3	51
35	G34620	2.4	1.11	30	80	<5	2.87	2	9	95	1865	3.61	<10	0.68	1314	22	0.01	4	1100	36	5	<20	244	0.03	<10	20	<10	7	66
QC DATA:																													
Repeat:																													
1	G34586	3.2	0.41	25	30	<5	0.16	4	6	162	2557	3.26	<10	0.13	117	40	<0.01	8	730	38	10	<20	15	<0.01	<10	12	<10	<1	34
10	G34586	10.1	0.93	20	75	<5	1.50	6	8	135	2916	3.39	<10	0.44	879	31	<0.01	6	880	78	5	<20	68	0.01	<10	16	<10	4	190
19	G34604	2.0	0.53	25	85	<5	1.92	1	6	94	2686	1.84	<10	0.19	679	41	<0.01	3	720	28	5	<20	66	<0.01	<10	7	<10	4	48
Resplit:																													
1	G34586	3.1	0.41	15	40	<5	0.14	3	6	159	2707	3.33	<10	0.11	109	41	<0.01	8	630	36	<5	<20	16	<0.01	<10	11	<10	<1	33
Standard:																													
Pb113		11.4	0.20	40	70	<5	1.88	46	2	7	2355	1.10	<10	0.13	1557	64	0.02	3	80	5528	30	<20	83	<0.01	<10	10	<10	<1	6959

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/7184
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5489

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07043
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36676	0.06	0.002
2	G36677	0.20	0.006
3	G36678	0.08	0.002
4	G36679	0.31	0.009
5	G36680	0.18	0.005
6	G36681	0.09	0.003
7	G36682	0.43	0.013
8	G36683	0.12	0.003
9	G36684	0.30	0.009
10	G36685	0.30	0.009
11	G36686	0.28	0.008
12	G36687	0.26	0.008
13	G36688	0.27	0.008
14	G36689	0.33	0.010
15	G36690	0.10	0.003
16	G36691	0.18	0.005
17	G36692	0.18	0.005
18	G36693	1.07	0.031
19	G36694	0.18	0.005
20	G36695	0.19	0.006
21	G36696	0.09	0.003
22	G36697	0.19	0.006
23	G36698	1.12	0.033
24	G36699	0.22	0.006
25	G36700	<0.03	<0.001
26	G36701	0.26	0.008
27	G36702	0.12	0.003

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 17-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G36703	0.14	0.004
29	G36704	0.07	0.002
30	G36705	0.10	0.003
31	G36706	0.26	0.008
32	G36707	0.20	0.006
33	G36708	0.24	0.007
34	G36709	<0.03	<0.001
35	G36710	<0.03	<0.001

QC DATA:

Repeat:

1	G36676	0.06	0.002
7	G36682	0.46	0.013
10	G36685	0.30	0.009
11	G36686	0.32	0.009
18	G36693	1.14	0.033
19	G36694	0.17	0.005
23	G36698	1.22	0.036

Resplits:

1	G36676	0.04	0.001

Standard:

Si25		1.78	0.052

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

17-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5489

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07043
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36676	0.6	0.95	<5	60	<5	1.67	<1	13	64	475	3.45	<10	1.06	827	5	0.07	15	810	30	<5	<20	149	0.05	<10	168	<10	1	37
2	G36677	1.5	1.12	10	55	<5	0.84	1	19	52	1152	4.22	<10	1.46	437	27	0.07	28	960	52	10	<20	89	0.06	<10	118	<10	3	44
3	G36678	1.2	1.11	15	60	<5	1.16	<1	11	55	827	3.04	<10	1.18	722	5	0.03	15	940	40	<5	<20	118	0.06	<10	182	<10	3	42
4	G36679	1.1	1.07	<5	80	<5	1.19	3	23	47	1504	8.44	<10	1.16	813	14	0.05	23	560	44	15	<20	93	0.05	<10	338	<10	<1	71
5	G36680	1.1	1.13	15	65	<5	1.94	<1	31	63	1072	4.40	<10	1.02	1132	7	0.04	12	450	42	<5	<20	155	0.05	<10	171	<10	<1	84
6	G36681	0.9	0.95	<5	60	<5	2.84	<1	25	71	884	4.55	<10	0.96	1055	<1	0.07	14	420	54	<5	<20	249	0.08	<10	328	<10	<1	67
7	G36682	1.3	1.56	25	90	<5	3.71	2	31	59	1583	7.82	<10	1.97	1413	8	0.06	45	890	38	5	<20	314	0.09	<10	434	<10	<1	75
8	G36683	1.3	1.27	<5	55	<5	3.35	2	30	55	1372	7.92	<10	1.73	1223	7	0.07	38	980	30	10	<20	305	0.08	<10	458	<10	<1	61
9	G36684	2.0	1.32	55	55	<5	2.33	2	21	53	866	5.20	<10	1.57	1943	8	0.02	23	610	50	30	<20	176	0.05	<10	217	<10	1	58
10	G36685	2.6	1.20	55	50	<5	4.86	2	18	50	787	4.44	<10	1.97	5949	8	0.02	23	860	46	40	<20	315	0.08	<10	237	<10	2	78
11	G36686	3.2	1.06	35	50	<5	1.91	<1	19	52	2652	3.56	10	0.69	187	200	0.03	8	430	58	<5	<20	48	0.03	<10	44	<10	4	276
12	G36687	1.7	1.69	5	90	<5	3.77	3	18	49	1726	8.40	<10	2.35	1494	12	0.04	20	500	36	15	<20	336	0.09	<10	483	<10	<1	67
13	G36688	2.0	1.77	35	70	<5	3.37	1	17	52	1057	5.90	<10	2.38	1770	8	0.04	17	660	50	10	<20	287	0.09	<10	532	<10	<1	114
14	G36689	1.2	1.91	<5	100	<5	3.05	2	20	58	1906	5.71	<10	2.53	1155	19	0.05	23	710	42	25	<20	255	0.08	<10	439	<10	<1	64
15	G36690	0.5	1.33	<5	75	<5	3.20	<1	16	63	786	3.91	<10	1.77	1027	4	0.09	16	660	38	<5	<20	248	0.08	<10	311	<10	2	47
16	G36691	0.9	1.69	35	80	<5	3.26	1	24	59	990	4.88	<10	2.23	1502	11	0.06	35	700	56	10	<20	234	0.08	<10	266	<10	2	93
17	G36692	1.1	1.74	30	75	<5	3.12	<1	22	55	1054	4.86	<10	2.33	1480	11	0.06	31	770	70	<5	<20	224	0.09	<10	255	<10	2	96
18	G36693	5.8	2.21	40	80	<5	3.04	2	20	59	1355	6.15	<10	3.14	1785	14	0.02	39	800	74	25	<20	223	0.10	<10	257	<10	3	104
19	G36694	1.3	0.82	40	55	<5	1.90	<1	19	64	972	3.30	<10	0.63	809	21	0.04	31	870	36	<5	<20	131	0.04	<10	61	<10	5	29
20	G36695	0.7	1.03	50	55	<5	1.91	<1	13	49	323	3.22	<10	0.86	800	24	0.04	20	820	32	15	<20	127	0.04	<10	62	<10	5	42
21	G36696	0.5	0.94	35	60	<5	2.52	<1	11	46	451	2.47	<10	0.82	1055	40	0.05	15	1290	32	<5	<20	161	0.05	<10	47	<10	8	35
22	G36697	0.7	0.81	30	45	<5	2.83	<1	11	51	242	2.75	<10	0.63	1170	15	0.04	22	1110	30	<5	<20	165	0.04	<10	42	<10	6	23
23	G36698	3.1	0.94	55	50	<5	1.59	1	17	50	846	4.12	<10	0.69	812	27	0.03	36	830	50	15	<20	106	0.03	<10	44	<10	6	31
24	G36699	0.5	0.77	40	50	<5	1.20	<1	18	62	649	2.23	<10	0.55	511	46	0.07	16	610	24	<5	<20	83	0.04	<10	39	<10	5	22
25	G36700	<0.2	0.97	20	225	<5	0.52	<1	6	79	6	2.03	<10	0.56	512	2	0.08	4	870	10	<5	<20	75	0.08	<10	43	<10	<1	42

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36701	0.4	1.06	40	60	<5	1.42	<1	13	55	342	2.93	<10	0.90	570	15	0.06	16	950	40	5	<20	96	0.03	<10	50	<10	5	29
27	G36702	0.5	1.11	25	55	<5	3.60	<1	13	58	433	2.69	<10	1.12	1595	12	0.08	19	1030	28	5	<20	155	0.04	<10	61	<10	7	36
28	G36703	1.2	1.16	35	55	<5	2.26	1	13	44	422	4.58	<10	1.29	1455	17	0.04	24	1250	60	15	<20	140	0.04	<10	51	<10	5	68
29	G36704	0.7	1.19	45	65	<5	1.23	<1	7	65	319	1.99	<10	1.04	714	31	0.07	17	1110	34	10	<20	79	0.04	<10	56	<10	6	27
30	G36705	1.3	1.15	45	50	<5	1.36	<1	14	70	601	2.24	<10	1.01	849	44	0.07	20	820	38	10	<20	94	0.03	<10	39	<10	6	29
31	G36706	2.8	0.79	45	50	<5	1.78	<1	14	54	508	2.39	<10	0.64	938	77	0.06	20	880	60	10	<20	117	0.03	<10	28	<10	5	95
32	G36707	2.5	0.62	75	50	<5	3.89	<1	7	51	531	2.68	<10	0.09	1899	42	<0.01	13	680	136	15	<20	187	0.03	<10	61	<10	5	46
33	G36708	5.1	0.50	75	30	<5	3.69	3	8	89	1000	2.39	<10	0.08	2020	18	<0.01	16	590	184	40	<20	255	0.01	<10	43	<10	5	297
34	G36709	0.6	0.27	30	45	<5	1.24	<1	2	72	22	1.43	<10	0.03	893	13	0.03	4	70	56	<5	<20	86	0.01	<10	19	<10	<1	38
35	G36710	0.5	0.27	30	60	<5	1.31	<1	2	80	12	1.07	<10	0.03	822	9	0.05	<1	60	38	<5	<20	111	0.02	<10	13	<10	<1	14
QC DATA:																													
Repeat:																													
1	G36676	0.6	0.97	5	65	<5	1.68	<1	13	68	483	3.47	<10	1.06	835	4	0.07	14	820	32	<5	<20	156	0.06	<10	174	<10	3	37
10	G36685	2.7	1.17	75	50	<5	4.85	<1	18	51	767	4.38	<10	1.92	5883	7	0.02	22	890	50	35	<20	313	0.08	<10	229	<10	3	78
19	G36694	1.4	0.88	45	55	<5	1.96	<1	19	68	992	3.40	<10	0.65	828	22	0.04	32	890	36	<5	<20	129	0.04	<10	66	<10	4	30
Resplit:																													
1	G36676	0.6	1.01	10	60	<5	1.77	2	15	65	498	3.64	<10	1.13	848	5	0.07	15	910	30	15	<20	160	0.05	<10	179	<10	2	41
Standard:																													
Pb113		11.2	0.25	45	55	<5	1.62	32	2	6	2223	1.02	<10	0.10	1593	61	0.02	4	80	5372	30	<20	86	<0.01	<10	8	40	<1	6943

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl/jl
df/5498S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007- 5490

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07044
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36711	0.06	0.002
2	G36712	0.33	0.010
3	G36713	0.18	0.005
4	G36714	0.19	0.006
5	G36715	0.50	0.015
6	G36716	0.36	0.010
7	G36717	1.18	0.034
8	G36718	0.08	0.002
9	G36719	0.04	0.001
10	G36720	0.04	0.001
11	G36721	<0.03	<0.001
12	G36722	0.08	0.002
13	G36723	0.07	0.002
14	G36724	0.07	0.002
15	G36725	0.06	0.002
16	G36726	0.19	0.006
17	G36727	0.14	0.004
18	G36728	0.58	0.017
19	G36729	0.46	0.013
20	G36730	0.61	0.018
21	G36731	0.44	0.013
22	G36732	0.08	0.002
23	G36733	0.13	0.004
24	G36734	0.07	0.002
25	G36735	1.04	0.030
26	G36736	0.08	0.002

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5490 17-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	G36737	0.15	0.004
28	G36738	0.18	0.005
29	G36739	0.07	0.002
30	G36740	0.26	0.008
31	G36741	0.24	0.007
32	G36742	0.23	0.007
33	G36743	0.09	0.003
34	G36744	0.03	0.001
35	G36745	0.06	0.002

QC DATA:

Repeat:

1	G36711	0.05	0.001
5	G36715	0.50	0.015
6	G36716	0.36	0.010
7	G36717	1.18	0.034
10	G36720	0.05	0.001
19	G36729	0.45	0.013

Resplits:

1	G36711	0.05	0.001

Standard:

Si25		1.76	0.051

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5490

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07044
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36711	0.6	0.36	10	70	<5	1.37	<1	2	83	23	1.05	<10	0.05	825	17	0.08	2	50	42	<5	<20	132	0.05	<10	24	<10	1	27
2	G36712	2.9	2.01	100	55	<5	3.79	3	21	74	703	5.81	10	1.57	2555	34	0.03	25	890	206	40	<20	252	0.07	<10	182	<10	4	163
3	G36713	1.9	1.11	15	55	<5	2.63	<1	13	88	982	2.89	<10	0.61	1382	8	0.05	17	560	56	<5	<20	157	0.05	<10	138	<10	5	52
4	G36714	2.0	1.50	25	60	<5	3.79	<1	11	68	1341	3.03	<10	0.69	1845	26	0.02	16	680	80	<5	<20	202	0.06	<10	152	<10	10	60
5	G36715	5.0	1.45	20	60	<5	3.75	<1	12	59	1427	3.07	<10	0.82	2459	12	0.01	15	580	80	15	<20	196	0.05	<10	143	<10	6	96
6	G36716	4.7	1.28	10	65	<5	3.16	<1	12	50	941	3.03	<10	0.76	2441	<1	0.02	4	820	202	<5	<20	182	0.09	<10	103	<10	7	356
7	G36717	7.3	1.66	30	50	<5	2.68	7	69	67	1987	>10	<10	1.25	2894	23	0.02	38	520	242	70	<20	192	0.05	<10	195	<10	<1	116
8	G36718	0.5	0.37	5	55	<5	1.90	<1	3	70	160	1.23	<10	0.08	1108	10	0.01	4	100	20	<5	<20	143	0.02	<10	17	<10	<1	10
9	G36719	0.3	0.33	10	70	<5	2.61	<1	2	94	40	1.05	<10	0.11	1350	6	0.01	5	60	10	<5	<20	220	0.02	<10	14	<10	1	5
10	G36720	0.4	0.35	10	75	<5	1.64	<1	2	76	69	0.95	<10	0.03	670	14	0.02	<1	80	16	<5	<20	119	0.07	<10	13	<10	1	3
11	G36721	<0.2	1.10	10	260	15	0.66	1	7	120	4	2.22	<10	0.61	555	7	0.12	10	660	22	25	<20	109	0.09	<10	49	<10	3	44
12	G36722	1.2	0.60	10	40	<5	1.92	<1	3	89	150	1.65	10	0.23	897	23	0.06	4	70	46	<5	<20	162	0.02	<10	39	<10	<1	51
13	G36723	1.1	0.66	10	50	<5	2.34	<1	4	92	174	1.65	10	0.30	1113	34	0.06	5	100	54	5	<20	194	0.03	<10	46	<10	1	46
14	G36724	0.9	0.56	15	35	<5	1.56	<1	5	82	212	1.76	<10	0.25	933	28	0.05	5	270	34	5	<20	152	0.03	<10	53	<10	2	28
15	G36725	0.6	0.45	10	45	<5	1.47	<1	4	79	129	1.45	<10	0.19	924	20	0.07	1	130	26	<5	<20	135	0.04	<10	44	<10	1	20
16	G36726	2.3	1.06	20	55	<5	3.11	<1	10	60	1147	2.80	10	0.74	2082	12	0.02	9	600	60	15	<20	173	0.06	<10	127	<10	6	54
17	G36727	2.5	0.78	15	50	<5	2.91	<1	7	77	1133	2.41	<10	0.46	1652	17	0.05	<1	610	56	<5	<20	161	0.09	<10	86	<10	4	51
18	G36728	28.0	1.78	20	60	<5	5.01	6	22	84	2092	5.99	<10	1.97	2825	27	0.01	24	440	1508	65	<20	270	0.05	<10	870	<10	5	122
19	G36729	4.8	1.51	25	45	<5	2.59	2	18	74	1429	4.70	<10	1.43	1328	17	0.04	19	680	104	20	<20	117	0.12	<10	313	<10	5	146
20	G36730	4.2	1.63	20	55	<5	3.64	<1	17	82	3689	4.05	<10	1.66	1952	1	0.04	17	500	82	<5	<20	181	0.10	<10	294	<10	8	132
21	G36731	2.1	2.88	15	85	<5	2.98	2	16	67	1598	6.39	<10	3.12	2512	24	0.03	40	930	166	30	<20	149	0.11	<10	360	<10	6	227
22	G36732	1.3	2.38	15	70	<5	2.67	2	14	71	1006	5.16	<10	2.42	1643	22	0.05	39	1050	180	35	<20	147	0.09	<10	230	<10	6	185
23	G36733	1.7	2.39	10	170	<5	2.98	1	12	65	660	5.03	<10	2.27	1652	10	0.05	30	1080	280	20	<20	176	0.13	<10	325	<10	5	163
24	G36734	1.6	2.02	15	95	<5	2.42	2	15	74	1526	4.21	10	2.26	1282	20	0.05	42	880	190	35	<20	117	0.10	<10	227	<10	7	149
25	G36735	3.5	1.15	65	70	<5	0.77	3	18	59	3338	3.86	20	0.52	283	214	0.03	15	300	142	30	<20	32	0.04	<10	45	<10	5	160

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36736	1.3	1.46	20	65	<5	2.18	<1	14	77	1383	3.29	10	1.60	1206	56	0.05	14	650	102	<5	<20	111	0.09	<10	155	<10	9	98
27	G36737	2.8	1.74	35	45	<5	2.19	<1	15	89	1473	4.07	10	1.44	1382	15	0.03	31	670	240	10	<20	107	0.09	<10	252	<10	5	123
28	G36738	3.1	2.27	20	75	<5	3.96	2	13	79	1502	5.02	20	2.33	3208	17	0.02	41	810	322	20	<20	204	0.09	<10	380	<10	8	148
29	G36739	3.1	2.24	30	220	<5	2.43	<1	9	65	476	3.15	20	2.28	1578	11	0.04	56	830	844	20	<20	135	0.10	<10	229	<10	8	129
30	G36740	3.3	1.86	60	70	<5	4.52	1	12	57	1247	3.28	20	1.62	3025	49	0.01	27	650	522	30	<20	226	0.08	<10	272	<10	8	90
31	G36741	2.3	1.07	45	40	<5	4.83	<1	13	49	1492	2.95	<10	0.86	3368	12	0.01	16	450	100	10	<20	217	0.05	<10	50	<10	5	48
32	G36742	1.8	1.63	35	70	<5	3.09	<1	13	58	1448	2.57	10	0.84	1877	13	0.01	14	750	140	<5	<20	143	0.06	<10	120	<10	8	68
33	G36743	1.1	1.91	25	150	<5	2.96	2	13	69	1417	3.59	10	1.48	1407	20	0.03	35	760	92	30	<20	155	0.06	<10	214	<10	5	123
34	G36744	2.4	1.65	20	250	<5	2.34	<1	8	54	648	2.71	10	1.20	1250	36	0.03	19	820	348	10	<20	133	0.08	<10	113	<10	6	87
35	G36745	2.9	1.42	20	80	<5	3.53	2	11	56	3377	3.26	20	1.21	2045	95	0.02	25	600	258	50	<20	214	<0.01	<10	137	<10	9	91
QC DATA:																													
Repeat:																													
1	G36711	0.6	0.34	10	65	<5	1.39	<1	2	80	23	1.05	<10	0.06	831	16	0.07	4	60	44	<5	<20	128	0.02	<10	23	<10	1	28
10	G36720	0.3	0.33	10	65	<5	1.67	<1	2	75	72	0.96	<10	<0.01	680	11	0.02	<1	80	16	<5	<20	117	0.07	<10	12	<10	1	4
19	G36729	4.8	1.44	25	45	<5	2.63	<1	19	71	1419	4.77	<10	1.40	1339	13	0.04	16	730	112	<5	<20	119	0.11	<10	296	<10	5	151
Resplit:																													
1	G36711	0.5	0.33	15	75	<5	1.44	<1	2	99	26	1.07	<10	0.07	936	17	0.07	4	60	40	<5	<20	143	0.04	<10	23	<10	2	25
Standard:																													
Pb113		11.0	0.26	40	65	<5	1.72	38	2	6	2132	1.06	<10	0.10	1449	65	0.02	4	80	5512	15	<20	83	<0.01	<10	8	40	<1	6911

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5490
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AW 2007- 5491

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07045
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36746	0.34	0.010
2	G36747	0.11	0.003
3	G36748	0.32	0.009
4	G36749	0.46	0.013
5	G36750	0.14	0.004
6	G36751	0.11	0.003
7	G36752	0.39	0.011
8	G36753	0.61	0.018
9	G36754	0.19	0.006
10	G36755	<0.03	<0.001
11	G36756	0.15	0.004
12	G36757	0.06	0.002
13	G36758	0.08	0.002
14	G36759	0.08	0.002
15	G36760	0.13	0.004
16	G36761	0.05	0.001
17	G36762	0.06	0.002
18	G36763	0.16	0.005
19	G36764	0.12	0.003
20	G36765	0.20	0.006
21	G36766	1.05	0.031
22	G36767	0.45	0.013
23	G36768	0.13	0.004
24	G36769	1.89	0.055
25	G36770	0.20	0.006
26	G36771	0.27	0.008
27	G36772	0.37	0.011

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 17-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G36773	0.12	0.003
29	G36774	0.09	0.003
30	G36775	0.12	0.003
31	G36776	0.13	0.004
32	G36777	0.14	0.004
33	G36778	0.38	0.011
34	G36779	0.15	0.004
35	G36780	0.05	0.001

QC DATA:

Repeat:

1	G36746	0.33	0.010
10	G36755	0.14	0.004
19	G36764	0.22	0.006

Resplits:

1	G36746	0.28	0.008

Standard:

Si25		1.78	0.052

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5491

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07045
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36746	2.5	1.21	40	95	<5	3.14	<1	11	56	1647	3.12	20	1.17	1709	45	0.04	16	1000	186	<5	<20	163	0.03	<10	281	<10	9	104
2	G36747	3.4	1.48	40	140	<5	3.68	<1	10	56	1681	3.25	10	1.72	1953	87	0.03	28	850	322	10	<20	204	0.04	<10	348	<10	8	159
3	G36748	2.9	1.32	50	85	<5	4.09	1	11	50	1871	3.44	10	1.27	2233	18	0.02	19	780	200	15	<20	245	0.04	<10	367	<10	7	115
4	G36749	2.8	1.08	40	60	<5	3.92	<1	10	70	1411	3.10	<10	0.65	2471	6	0.01	14	840	74	<5	<20	217	0.03	<10	80	<10	4	50
5	G36750	1.0	1.46	50	115	<5	1.72	<1	11	73	827	2.75	10	0.96	924	34	0.04	23	1130	78	5	<20	105	0.03	<10	91	<10	5	81
6	G36751	2.2	1.59	60	115	<5	2.61	<1	14	66	1600	3.34	<10	1.21	1204	12	0.04	37	1110	216	<5	<20	141	0.05	<10	92	<10	4	90
7	G36752	1.5	1.69	50	85	<5	2.06	1	21	80	963	4.84	10	1.18	1278	60	0.04	41	1050	146	20	<20	139	0.04	<10	125	<10	3	98
8	G36753	2.7	0.63	60	55	<5	2.42	<1	8	59	711	2.39	<10	0.24	1603	33	0.02	22	1080	54	10	<20	153	0.02	<10	37	<10	5	76
9	G36754	3.2	0.94	50	65	<5	2.87	<1	6	65	666	1.89	<10	0.52	2477	36	0.02	12	870	94	<5	<20	201	0.03	<10	60	<10	5	43
10	G36755	<0.2	1.04	25	230	10	0.63	<1	7	144	9	2.21	<10	0.58	554	3	0.13	7	860	26	<5	<20	82	0.09	<10	47	<10	1	44
11	G36756	1.6	1.28	60	60	<5	2.13	<1	13	55	1031	2.73	<10	0.83	1426	17	0.04	18	1080	58	5	<20	165	0.04	<10	93	<10	5	69
12	G36757	2.0	1.23	55	80	<5	2.83	<1	15	73	1875	2.87	10	0.78	1415	63	0.03	17	570	56	10	<20	200	0.03	<10	123	<10	4	61
13	G36758	1.3	1.14	55	60	<5	2.85	<1	17	51	689	2.41	10	0.69	1428	62	0.03	21	1000	60	10	<20	200	0.03	<10	72	<10	6	52
14	G36759	1.7	0.85	40	50	<5	3.09	<1	13	75	678	1.93	20	0.33	2011	57	0.02	16	900	72	<5	<20	210	0.02	<10	44	<10	5	148
15	G36760	0.7	0.88	45	35	<5	2.50	<1	10	57	297	2.55	<10	0.42	1616	9	0.01	9	1190	38	15	<20	171	0.02	<10	43	<10	3	40
16	G36761	0.7	0.28	50	45	<5	3.01	<1	<1	97	88	1.13	10	0.06	1471	7	0.02	5	80	34	15	<20	226	0.01	<10	6	<10	<1	40
17	G36762	0.5	0.20	30	45	<5	1.58	<1	<1	73	59	1.16	<10	0.02	839	16	0.04	3	90	56	5	<20	147	0.01	<10	5	<10	<1	88
18	G36763	0.7	0.31	30	30	<5	1.90	<1	2	73	140	1.66	<10	0.09	1270	10	0.02	3	170	62	<5	<20	163	0.04	<10	10	<10	<1	55
19	G36764	1.0	0.47	30	30	<5	1.29	<1	2	69	207	2.62	<10	0.17	875	20	0.01	4	120	62	<5	<20	110	0.02	<10	22	<10	<1	60
20	G36765	2.9	0.93	40	35	<5	6.76	<1	9	41	598	2.46	<10	0.75	3690	42	<0.01	5	880	214	<5	<20	408	0.05	<10	40	<10	8	53
21	G36766	2.1	0.88	45	35	<5	3.31	<1	11	67	1187	2.83	<10	0.51	2011	24	0.02	6	1010	44	<5	<20	236	0.03	<10	42	<10	3	38
22	G36767	1.3	1.00	35	50	<5	2.87	<1	10	45	701	2.81	<10	0.57	1788	42	0.02	6	1200	52	10	<20	202	0.03	<10	51	<10	3	41
23	G36768	1.7	0.73	60	40	<5	2.39	<1	10	57	655	2.41	10	0.24	1161	15	0.03	4	1270	54	<5	<20	172	0.05	<10	36	<10	4	33
24	G36769	3.9	1.05	55	40	<5	0.99	2	21	55	8593	4.05	<10	0.59	198	585	0.04	62	90	68	25	<20	45	<0.01	<10	42	<10	4	71
25	G36770	2.3	0.60	75	15	<5	2.88	<1	10	63	835	2.83	20	0.17	1292	11	0.01	10	1030	68	<5	<20	172	0.01	<10	31	<10	2	69

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36771	2.3	0.50	45	20	<5	3.75	<1	12	54	1007	3.44	<10	0.18	1789	15	0.02	10	1190	68	<5	<20	317	0.03	<10	18	<10	5	25
27	G36772	1.5	0.91	50	30	<5	2.11	<1	16	39	163	2.82	<10	0.84	1075	10	0.02	24	1120	54	<5	<20	284	0.04	<10	18	<10	5	65
28	G36773	0.5	1.05	45	45	<5	1.55	<1	19	38	105	3.76	<10	1.06	1060	4	0.02	37	1270	34	10	<20	124	0.08	<10	17	<10	7	66
29	G36774	0.8	0.88	90	40	10	1.27	<1	18	47	136	3.69	<10	0.84	918	5	0.02	27	1090	32	15	<20	93	0.07	<10	17	<10	3	65
30	G36775	1.3	0.84	70	35	<5	1.66	<1	16	67	133	3.69	<10	0.80	1326	3	0.02	24	830	32	<5	<20	109	0.09	<10	21	<10	2	73
31	G36776	1.3	0.83	50	40	<5	1.56	<1	16	59	119	3.33	<10	0.81	1419	3	0.01	21	880	32	<5	<20	98	0.06	<10	16	<10	3	73
32	G36777	1.4	0.69	65	30	<5	0.35	<1	21	64	195	4.47	<10	0.61	528	5	<0.01	25	910	30	<5	<20	26	0.02	<10	15	<10	<1	49
33	G36778	1.1	0.54	50	35	<5	0.26	<1	17	80	73	3.99	<10	0.34	270	5	<0.01	26	1110	50	<5	<20	26	0.02	<10	14	<10	<1	31
34	G36779	0.6	0.25	40	30	10	0.18	<1	9	87	17	2.61	<10	0.01	67	5	<0.01	15	580	52	<5	<20	29	0.01	<10	4	<10	<1	26
35	G36780	1.5	0.44	45	30	<5	0.82	<1	11	83	203	2.13	<10	0.30	632	4	0.03	13	610	70	<5	<20	57	0.03	<10	10	<10	1	138
QC DATA:																													
Repeat:																													
1	G36746	2.3	1.22	40	110	<5	3.07	<1	11	58	1618	3.06	20	1.16	1670	45	0.04	18	980	182	15	<20	165	0.05	<10	279	<10	9	99
10	G36755	<0.2	1.05	35	235	<5	0.65	<1	7	146	9	2.22	<10	0.59	555	6	0.13	10	860	26	10	<20	86	0.08	<10	48	<10	<1	44
19	G36764	1.0	0.50	30	25	<5	1.32	<1	3	73	215	2.69	<10	0.18	899	19	<0.01	2	120	68	<5	<20	122	0.03	<10	23	<10	<1	62
Resplit:																													
1	G36746	2.5	1.25	35	95	<5	3.15	1	10	61	1695	3.18	10	1.19	1830	49	0.04	16	910	182	<5	<20	166	0.03	<10	280	<10	8	106
Standard:																													
Pb113		11.0	0.26	40	60	<5	1.61	32	2	5	2230	1.01	<10	0.09	1585	69	0.02	3	80	5376	25	<20	83	<0.01	<10	8	40	<1	6926

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
dl/5489S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5492

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07046
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36781	0.18	0.005
2	G36782	0.21	0.006
3	G36783	0.09	0.003
4	G36784	0.09	0.003
5	G36785	0.12	0.003
6	G36786	0.13	0.004
7	G36787	0.12	0.003
8	G36788	0.16	0.005
9	G36789	0.10	0.003
10	G36790	0.14	0.004
11	G36791	0.08	0.002
12	G36792	0.09	0.003
13	G36793	0.10	0.003
14	G36794	0.09	0.003
15	G36795	0.10	0.003
16	G36796	0.31	0.009
17	G36797	0.15	0.004
18	G36798	0.18	0.005
19	G36799	0.12	0.003
20	G36800	0.10	0.003
21	G36801	0.10	0.003
22	G36802	0.08	0.002
23	G36803	0.08	0.002
24	G36804	0.07	0.002
25	G36805	0.07	0.002
26	G36806	0.06	0.002
27	G36807	0.09	0.003

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 5492 17-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G36808	0.11	0.003
29	G36809	0.09	0.003
30	G36810	<0.03	<0.001
31	G36811	0.10	0.003
32	G36812	0.09	0.003
33	G36813	0.07	0.002
34	G36814	0.09	0.003
35	G36815	0.10	0.003

QC DATA:

Repeat:

1	G36781	0.20	0.006
10	G36790	0.14	0.004
19	G36799	0.13	0.004

Resplits:

1	G36781	0.15	0.004

Standard:

Si25		1.79	0.052

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

17-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5492

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07046
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36781	2.6	0.45	35	30	10	0.59	2	26	81	156	4.42	<10	0.16	337	30	0.01	21	1190	96	<5	<20	47	0.03	<10	9	<10	<1	46
2	G36782	1.8	1.27	25	60	<5	0.91	1	21	58	412	4.44	<10	1.22	970	8	0.01	37	1970	36	10	<20	57	0.06	<10	26	<10	5	109
3	G36783	0.6	0.68	20	45	10	2.12	3	17	63	62	5.47	<10	0.55	774	9	0.02	6	2170	72	10	<20	154	0.06	<10	23	<10	3	67
4	G36784	0.9	0.66	30	35	10	1.32	3	17	62	77	5.29	<10	0.51	459	7	0.02	7	2110	52	10	<20	93	0.04	<10	21	<10	2	64
5	G36785	0.4	0.91	15	35	10	2.01	2	19	54	97	5.01	<10	0.96	665	7	0.04	8	2200	40	15	<20	157	0.07	<10	52	<10	3	69
6	G36786	0.5	0.89	25	40	<5	2.06	4	18	59	113	4.95	<10	0.95	687	9	0.04	12	2300	48	25	<20	168	0.06	<10	54	<10	3	80
7	G36787	0.7	0.93	25	45	25	1.71	3	17	75	111	4.48	<10	0.94	691	6	0.04	6	2350	52	<5	<20	143	0.08	<10	50	<10	5	98
8	G36788	0.8	0.91	15	45	10	1.46	2	17	63	104	4.86	<10	0.91	602	5	0.04	7	2250	52	<5	<20	110	0.07	<10	50	<10	3	69
9	G36789	0.3	0.82	20	45	25	1.16	2	18	83	89	5.16	<10	0.87	431	7	0.05	9	2120	50	<5	<20	106	0.07	<10	46	<10	3	59
10	G36790	0.5	1.00	15	50	15	1.64	1	17	69	83	4.84	<10	1.01	587	4	0.05	5	2340	44	10	<20	126	0.09	<10	55	<10	3	66
11	G36791	0.2	0.92	40	45	25	1.94	1	18	62	75	5.03	<10	0.95	595	5	0.05	7	2340	40	10	<20	138	0.10	<10	52	<10	3	60
12	G36792	0.7	0.76	55	55	10	2.24	2	19	63	130	5.56	<10	0.64	589	6	0.03	7	2340	40	15	<20	156	0.07	<10	38	<10	5	51
13	G36793	1.7	0.80	80	45	15	2.38	4	19	73	277	5.52	<10	0.70	700	5	0.03	5	2430	52	25	<20	179	0.07	<10	44	<10	4	71
14	G36794	1.0	0.53	45	40	20	2.15	3	17	80	74	5.95	<10	0.26	566	8	0.01	6	2220	90	<5	<20	146	0.04	<10	16	<10	2	39
15	G36795	1.2	0.77	70	35	10	1.68	3	20	60	187	5.28	<10	0.71	463	4	0.03	5	2490	36	15	<20	118	0.07	<10	33	<10	4	55
16	G36796	3.2	1.21	40	55	<5	1.09	3	24	66	2665	3.94	30	0.72	223	215	0.04	11	610	66	15	<20	65	0.07	<10	46	<10	7	264
17	G36797	0.4	0.66	70	50	15	1.65	3	21	66	123	5.89	<10	0.51	418	9	0.03	12	2680	48	30	<20	120	0.04	<10	27	<10	4	37
18	G36798	0.5	0.49	75	45	20	1.32	2	21	62	206	4.82	<10	0.19	289	5	0.02	7	2530	38	10	<20	80	0.05	<10	16	<10	5	28
19	G36799	0.3	0.62	45	60	35	0.96	2	18	93	55	6.26	<10	0.35	225	8	0.02	9	2190	54	10	<20	94	0.05	<10	18	<10	4	22
20	G36800	0.3	0.52	60	65	40	1.10	1	20	83	64	5.94	<10	0.21	227	8	0.03	7	2280	38	<5	<20	85	0.06	<10	14	<10	5	17
21	G36801	0.5	0.65	65	55	30	1.33	2	19	66	95	5.86	<10	0.47	312	3	0.03	7	2320	36	5	<20	85	0.07	<10	21	<10	6	32
22	G36802	0.6	0.70	95	55	15	1.13	3	21	78	214	6.03	<10	0.54	291	7	0.03	8	2390	36	20	<20	72	0.05	<10	20	<10	5	40
23	G36803	0.4	0.74	50	55	35	1.35	2	20	84	72	5.80	<10	0.61	342	5	0.03	6	2420	42	5	<20	87	0.06	<10	24	<10	5	35
24	G36804	0.2	0.68	50	55	45	1.68	1	20	89	33	5.35	<10	0.52	383	7	0.03	7	2410	38	10	<20	109	0.05	<10	23	<10	6	27
25	G36805	<0.2	0.77	50	50	35	1.20	2	19	87	31	5.56	<10	0.67	315	5	0.03	7	2450	42	5	<20	85	0.04	<10	28	<10	6	34

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36806	<0.2	0.60	45	45	35	2.61	1	19	96	31	5.50	<10	0.37	617	6	0.02	6	2300	44	<5	<20	140	0.05	<10	20	<10	5	22
27	G36807	0.8	0.70	55	50	40	2.32	2	20	79	100	6.79	<10	0.56	666	8	0.02	10	2470	78	15	<20	138	0.05	<10	27	<10	5	60
28	G36808	0.7	0.88	75	50	15	2.17	2	19	77	82	5.75	<10	0.78	785	6	0.01	10	2630	58	10	<20	144	0.05	<10	36	<10	5	51
29	G36809	0.6	0.54	50	45	45	0.96	1	22	94	47	7.62	<10	0.22	260	5	0.01	7	2340	52	<5	<20	93	0.04	<10	15	<10	<1	20
30	G36810	<0.2	1.11	25	260	20	0.57	<1	8	90	5	2.09	10	0.62	550	4	0.08	5	1480	16	5	<20	96	0.10	<10	49	<10	4	44
31	G36811	0.4	0.70	50	50	45	1.46	2	18	97	72	6.05	<10	0.58	486	10	0.01	8	2130	50	15	<20	111	0.04	<10	16	<10	5	35
32	G36812	0.4	0.70	50	60	40	1.19	2	21	89	70	6.35	<10	0.54	377	9	0.01	9	2420	56	10	<20	75	0.04	<10	16	<10	6	34
33	G36813	0.5	0.77	55	50	40	1.38	2	22	93	54	5.82	<10	0.60	454	7	0.01	7	2520	126	10	<20	73	0.04	<10	19	<10	5	37
34	G36814	0.2	0.48	30	65	30	2.25	2	21	89	19	6.81	<10	0.14	602	9	0.01	8	2070	62	<5	<20	110	0.04	<10	14	<10	3	43
35	G36815	0.6	0.54	50	45	20	1.74	2	16	97	60	5.40	<10	0.27	586	18	0.01	6	2540	46	<5	<20	129	0.04	<10	14	<10	4	26
QC DATA:																													
Repeat:																													
1	G36781	2.6	0.42	35	30	15	0.61	2	27	79	166	4.59	<10	0.15	349	31	0.01	20	1270	102	<5	<20	48	0.03	<10	9	<10	<1	47
10	G36790	0.4	0.95	35	45	10	1.65	1	17	66	83	4.91	<10	0.98	582	4	0.05	7	2420	44	<5	<20	124	0.08	<10	54	<10	2	67
19	G36799	0.3	0.58	55	60	40	0.97	3	19	91	56	6.35	<10	0.34	225	10	0.02	10	2320	56	10	<20	99	0.04	<10	18	<10	4	22
Resplit:																													
1	G36781	3.2	0.45	25	35	20	0.60	2	26	89	158	4.83	<10	0.16	337	26	<0.01	23	1110	100	<5	<20	47	0.02	<10	9	<10	<1	44
Standard:																													
Pb113		11.0	0.24	45	75	<5	1.63	53	2	7	2338	1.13	<10	0.14	1588	68	0.02	4	80	5516	15	<20	83	<0.01	<10	11	<10	<1	7055

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/7184
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5499

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

29-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07047
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34656	0.60	0.017
2	G34657	0.58	0.017
3	G34658	0.65	0.019
4	G34659	0.76	0.022
5	G34660	0.73	0.021
6	G34661	0.62	0.018
7	G34662	0.58	0.017
8	G34663	0.52	0.015
9	G34664	0.47	0.014
10	G34665	0.68	0.020
11	G34666	0.40	0.012
12	G34667	0.25	0.007
13	G34668	0.64	0.019
14	G34669	0.87	0.025
15	G34670	<0.03	<0.001
16	G34671	0.64	0.019
17	G34672	0.41	0.012
18	G34673	0.36	0.010
19	G34674	0.27	0.008
20	G34675	0.70	0.020
21	G34676	0.45	0.013
22	G34677	0.80	0.023
23	G34678	0.06	0.002
24	G34679	0.08	0.002
25	G34680	0.08	0.002
26	G34681	0.15	0.004
27	G34682	0.13	0.004

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 29-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G34683	0.16	0.005
29	G34684	0.08	0.002
30	G34685	0.04	0.001
31	G34686	0.03	0.001
32	G34687	0.05	0.001
33	G34688	0.11	0.003
34	G34689	0.32	0.009
35	G34690	0.26	0.008

QC DATA:

Repeat:

1	G34656	0.58	0.017
10	G34665	0.63	0.018
19	G34674	0.26	0.008

Resplits:

1	G34656	0.50	0.015

Standard:

OXi54		1.84	0.054

AU: 30g FA/AA-Finish

Lydia Bradley

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

22-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5499

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07047
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34656	2.4	1.05	10	40	<5	1.27	<1	7	141	1341	3.57	<10	0.71	689	58	0.02	5	1130	28	<5	<20	92	<0.01	<10	27	<10	6	92
2	G34657	3.6	0.76	20	20	<5	0.97	1	8	108	1909	3.66	<10	0.51	499	284	0.02	4	1090	30	<5	<20	72	<0.01	<10	18	<10	6	77
3	G34658	3.7	0.76	15	25	<5	0.84	3	9	155	2120	3.25	<10	0.51	504	126	0.02	5	970	62	<5	<20	52	<0.01	<10	18	<10	5	159
4	G34659	2.2	0.98	10	30	<5	1.05	7	9	132	2330	3.15	<10	0.73	642	108	0.02	5	1120	18	<5	<20	77	<0.01	<10	27	<10	6	201
5	G34660	2.6	0.96	10	30	<5	1.11	<1	9	127	2395	3.29	<10	0.77	634	111	0.02	5	1100	22	<5	<20	85	<0.01	<10	26	<10	6	60
6	G34661	1.8	1.09	15	30	<5	0.92	2	9	107	1489	3.81	<10	0.88	633	77	0.02	4	1160	48	<5	<20	75	<0.01	<10	31	<10	6	115
7	G34662	1.6	1.29	15	35	<5	1.87	<1	9	93	1340	4.58	<10	0.94	918	57	0.02	3	1300	22	<5	<20	113	<0.01	<10	34	<10	7	102
8	G34663	1.8	0.92	10	30	<5	2.32	<1	8	91	1407	3.17	<10	0.69	908	88	0.02	4	1070	20	<5	<20	126	<0.01	<10	22	<10	7	73
9	G34664	2.1	0.90	15	25	<5	1.75	1	8	102	1529	3.92	<10	0.70	856	71	0.02	4	1050	22	<5	<20	111	<0.01	<10	28	<10	6	109
10	G34665	1.9	0.94	10	25	<5	0.88	<1	8	96	1678	3.65	<10	0.79	766	79	0.02	4	1120	18	<5	<20	96	<0.01	<10	28	<10	6	86
11	G34666	1.6	1.07	10	35	<5	1.99	1	11	93	1338	3.61	<10	0.79	1031	71	0.03	3	1080	20	<5	<20	165	0.01	<10	33	<10	5	128
12	G34667	1.1	0.89	10	40	<5	2.67	<1	9	69	738	3.21	<10	0.53	1141	25	0.02	3	1270	16	<5	<20	186	<0.01	<10	21	<10	6	82
13	G34668	2.2	0.99	70	35	<5	2.52	<1	10	81	828	3.62	<10	0.65	1156	32	0.01	3	1270	18	<5	<20	164	<0.01	<10	17	<10	6	79
14	G34669	5.2	1.00	35	30	<5	2.20	<1	11	106	1637	4.39	<10	0.78	1200	60	0.01	4	1180	20	<5	<20	128	<0.01	<10	20	<10	7	74
15	G34670	<0.2	1.06	5	240	<5	0.59	<1	7	92	4	2.10	<10	0.62	523	2	0.10	6	870	8	<5	<20	84	0.14	<10	42	<10	5	42
16	G34671	4.6	1.09	15	40	<5	2.96	<1	12	94	1905	3.16	<10	0.77	1241	56	0.01	5	1240	24	<5	<20	145	<0.01	<10	16	<10	8	73
17	G34672	4.3	1.26	20	35	<5	2.97	<1	10	110	1333	3.87	<10	0.94	1497	101	0.01	4	1180	28	<5	<20	149	<0.01	<10	22	<10	7	80
18	G34673	6.5	0.81	25	25	<5	2.87	<1	11	109	1293	3.97	<10	0.55	1381	86	0.02	4	1200	32	<5	<20	139	<0.01	<10	19	<10	7	59
19	G34674	3.7	1.29	15	45	<5	2.23	<1	9	87	1101	3.13	<10	0.98	1309	34	0.01	4	1330	20	<5	<20	134	<0.01	<10	22	<10	6	97
20	G34675	10.9	0.84	25	25	<5	4.05	6	10	85	1754	4.31	<10	0.68	1873	59	0.02	4	1160	370	<5	<20	235	<0.01	<10	19	<10	10	295
21	G34676	5.8	0.50	25	20	<5	2.21	4	11	98	907	4.22	<10	0.25	982	24	0.02	4	1170	124	<5	<20	123	<0.01	<10	10	<10	6	197
22	G34677	4.7	1.12	30	30	<5	5.68	3	8	77	990	3.98	<10	1.08	2873	27	0.02	3	1100	104	<5	<20	270	<0.01	<10	19	<10	9	192
23	G34678	1.2	0.33	5	70	<5	1.20	<1	11	76	1983	2.63	<10	0.28	417	23	0.02	15	1700	8	<5	<20	151	<0.01	<10	33	<10	9	21
24	G34679	1.6	0.69	10	75	<5	0.39	<1	20	80	2541	4.10	<10	0.29	333	30	0.02	19	1860	10	<5	<20	39	<0.01	<10	53	<10	7	29
25	G34680	0.8	0.41	10	65	<5	0.49	<1	13	53	1280	3.09	<10	0.13	396	9	0.04	12	1480	6	<5	<20	60	<0.01	<10	37	<10	6	18

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34681	0.4	0.41	10	65	<5	0.36	<1	9	44	738	2.84	<10	0.05	296	6	0.05	7	1460	8	<5	<20	48	<0.01	<10	23	<10	5	16
27	G34682	0.7	0.38	10	75	<5	0.82	<1	11	60	1040	3.02	<10	0.19	706	29	0.03	12	1590	8	<5	<20	113	<0.01	<10	31	<10	7	23
28	G34683	1.0	0.35	5	65	<5	0.64	<1	13	87	1671	2.94	<10	0.25	520	49	0.03	11	1370	6	<5	<20	139	<0.01	<10	30	<10	6	21
29	G34684	1.9	0.37	10	35	<5	1.21	<1	26	63	2703	5.69	<10	0.67	508	17	0.02	14	2130	10	<5	<20	179	<0.01	<10	46	<10	6	27
30	G34685	1.1	0.40	10	70	<5	0.86	<1	13	86	1701	3.79	<10	0.37	557	17	0.03	10	1690	8	<5	<20	131	<0.01	<10	51	<10	6	25
31	G34686	0.4	0.35	<5	100	<5	1.29	<1	7	39	477	2.54	<10	0.22	481	4	0.04	6	1390	6	<5	<20	144	<0.01	<10	25	<10	5	17
32	G34687	0.8	0.39	5	85	<5	1.43	<1	10	48	992	3.53	<10	0.35	578	5	0.03	5	1620	6	<5	<20	176	<0.01	<10	46	<10	6	20
33	G34688	1.8	0.50	10	35	<5	1.38	<1	26	37	2898	6.04	<10	0.71	601	5	0.03	6	2110	12	<5	<20	181	<0.01	<10	61	<10	7	44
34	G34689	1.5	0.33	20	45	<5	1.47	<1	16	56	1949	4.65	<10	0.52	601	4	0.03	5	1890	12	<5	<20	188	<0.01	<10	52	<10	6	29
35	G34690	2.1	0.38	5	35	<5	1.61	<1	20	44	3550	6.63	<10	0.70	615	7	0.03	6	2260	12	<5	<20	242	<0.01	<10	126	<10	8	50
QC DATA:																													
Repeat:																													
1	G34656	2.2	1.01	10	35	<5	1.24	<1	8	141	1343	3.54	<10	0.71	695	62	0.02	4	1160	18	<5	<20	92	<0.01	<10	26	<10	5	79
10	G34665	2.3	0.96	10	25	<5	0.83	<1	8	95	1681	3.73	<10	0.81	768	78	0.02	4	1100	18	<5	<20	98	<0.01	<10	28	<10	6	86
19	G34674	3.7	1.28	15	45	<5	2.17	<1	9	87	1081	3.19	<10	0.99	1298	34	0.02	4	1340	20	<5	<20	135	<0.01	<10	22	<10	6	96
Resplit:																													
1	G34656	2.1	1.10	10	40	<5	1.27	<1	8	140	1222	3.58	<10	0.78	630	52	0.02	3	1170	26	<5	<20	82	<0.01	<10	28	<10	6	87
Standard:																													
Pb113		11.4	0.26	40	55	<5	1.64	35	2	<1	2158	1.05	<10	0.11	1402	60	0.02	<1	90	5464	10	<20	80	0.01	<10	5	<10	1	6488

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

JJ/jl
dl/n5496
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5500

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

20-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07 - 048
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34691	0.33	0.010
2	G34692	0.23	0.007
3	G34693	0.26	0.008
4	G34694	0.12	0.003
5	G34695	0.14	0.004
6	G34696	0.07	0.002
7	G34697	0.05	0.001
8	G34698	0.09	0.003
9	G34699	0.11	0.003
10	G34700	0.04	0.001
11	G34701	0.46	0.013
12	G34702	0.20	0.006
13	G34703	0.11	0.003
14	G34704	0.54	0.016
15	G34705	0.29	0.008
16	G34706	0.08	0.002
17	G34707	0.06	0.002
18	G34708	0.04	0.001
19	G34709	0.31	0.009
20	G34710	0.33	0.010
21	G34711	0.17	0.005
22	G34712	0.19	0.006
23	G34713	0.22	0.006
24	G34714	<0.03	<0.001
25	G34715	0.15	0.004
26	G34716	0.21	0.006
27	G34717	0.13	0.004
28	G34718	0.31	0.009

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5500 20-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G34719	0.28	0.008
30	G34720	0.18	0.005
31	G34721	0.17	0.005
32	G34722	0.21	0.006
33	G34723	0.07	0.002
34	G34724	0.33	0.010
35	G34725	0.46	0.013

QC DATA:

Repeat:

1	G34691	0.30	0.009
10	G34700	0.04	0.001
19	G34709	0.30	0.009

Resplits:

1	G34691	0.47	0.014

Standard:

SI25		1.80	0.052

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

22-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5500

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07 - 048
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34691	2.1	0.36	<5	50	<5	1.31	2	27	50	2651	6.38	<10	0.46	635	10	0.02	10	2260	24	<5	<20	170	0.03	<10	65	<10	5	42
2	G34692	2.6	0.30	<5	50	<5	1.58	2	22	69	4892	6.02	<10	0.72	653	9	0.04	12	1480	12	5	<20	276	0.01	<10	233	<10	1	53
3	G34693	1.6	0.30	10	40	<5	1.89	<1	21	71	2558	4.64	<10	0.69	491	6	0.04	10	1600	14	<5	<20	302	0.02	<10	69	<10	2	34
4	G34694	1.7	0.34	<5	50	<5	1.38	2	22	64	2674	5.26	<10	0.60	478	17	0.04	11	1810	12	<5	<20	184	0.02	<10	115	<10	2	43
5	G34695	1.1	0.29	<5	70	<5	1.15	1	11	109	1443	2.93	<10	0.43	469	4	0.02	8	710	10	<5	<20	157	0.01	<10	75	<10	<1	26
6	G34696	0.9	0.31	<5	45	<5	2.15	1	17	79	1203	4.01	<10	0.98	800	5	0.02	10	1530	12	<5	<20	291	0.02	<10	43	<10	4	37
7	G34697	1.3	0.40	<5	50	<5	2.31	2	29	53	1846	5.25	<10	1.37	942	8	0.02	28	2020	14	5	<20	294	0.03	<10	40	<10	5	53
8	G34698	1.1	0.36	<5	80	<5	3.94	1	21	63	1280	4.23	<10	1.36	1725	6	0.01	16	1180	14	10	<20	344	0.03	<10	87	<10	4	46
9	G34699	0.8	0.35	<5	115	<5	6.59	2	20	64	922	5.05	<10	2.21	2255	4	0.01	12	1350	10	15	<20	456	0.04	<10	239	<10	4	69
10	G34700	0.5	0.41	<5	410	<5	2.88	<1	11	56	87	2.77	<10	0.86	1316	4	0.02	3	950	10	<5	<20	197	0.03	<10	29	<10	4	45
11	G34701	2.6	0.40	25	35	<5	4.80	2	25	75	907	5.56	<10	1.70	1858	6	0.01	20	1190	16	20	<20	366	0.04	<10	94	<10	3	52
12	G34702	2.0	0.42	25	35	<5	5.04	2	22	58	1388	4.69	<10	1.53	2010	9	0.01	17	1990	12	35	<20	389	0.03	<10	87	<10	6	63
13	G34703	1.0	0.35	15	80	<5	3.75	<1	12	45	493	2.42	<10	0.78	1542	106	<0.01	6	920	14	15	<20	308	0.02	<10	37	<10	4	35
14	G34704	2.2	0.25	55	60	<5	1.99	<1	8	115	1023	2.16	<10	0.46	1001	26	0.01	9	280	12	40	<20	147	0.02	<10	76	<10	1	40
15	G34705	2.2	0.25	20	45	<5	2.01	<1	12	123	2350	2.69	<10	0.55	957	12	0.01	11	130	10	<5	<20	137	0.01	<10	76	<10	<1	24
16	G34706	1.3	0.24	<5	100	<5	1.92	<1	7	130	1483	1.75	<10	0.47	885	6	<0.01	8	220	14	<5	<20	141	0.01	<10	64	<10	1	16
17	G34707	1.0	0.26	<5	80	<5	1.72	<1	8	113	1272	1.80	<10	0.47	783	5	0.01	8	150	10	<5	<20	130	0.01	<10	64	<10	<1	17
18	G34708	0.7	0.24	10	120	<5	2.15	<1	3	101	931	1.57	<10	0.60	970	5	0.01	4	290	6	5	<20	176	0.01	<10	54	<10	<1	17
19	G34709	2.2	0.19	70	45	<5	2.94	<1	7	122	917	1.82	<10	0.28	1196	4	<0.01	8	280	20	45	<20	242	0.02	<10	37	<10	3	24
20	G34710	2.3	0.19	75	35	<5	2.82	1	7	106	1153	1.87	<10	0.22	1045	5	<0.01	8	250	18	55	<20	248	0.01	<10	38	<10	3	26
21	G34711	1.5	0.21	30	50	<5	1.58	<1	4	106	869	1.66	<10	0.28	762	3	0.01	8	310	18	30	<20	132	0.01	<10	36	<10	1	25
22	G34712	2.2	0.22	35	100	<5	1.63	<1	2	122	699	1.05	<10	0.28	783	3	0.01	6	140	12	30	<20	168	0.01	<10	26	<10	2	70
23	G34713	2.3	0.21	30	35	<5	1.90	1	10	112	1550	2.44	<10	0.36	885	5	<0.01	14	110	38	10	<20	166	0.02	<10	47	<10	<1	71
24	G34714	<0.2	0.95	10	245	20	0.57	<1	7	96	7	2.12	<10	0.57	528	3	0.09	7	910	20	<5	<20	93	0.09	<10	45	<10	2	40
25	G34715	2.2	0.30	25	25	<5	2.76	1	13	69	103	3.08	<10	0.48	1286	20	0.04	7	1310	126	10	<20	273	0.02	<10	16	<10	3	64

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007- 5500 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34716	2.0	0.31	100	30	5	4.18	3	12	64	155	3.80	<10	0.32	1837	12	0.02	8	1200	122	65	<20	352	0.03	<10	17	<10	6	86
27	G34717	1.8	0.27	30	25	<5	1.62	2	13	55	145	3.64	<10	0.28	754	38	0.04	7	1290	82	30	<20	175	0.02	<10	16	<10	2	30
28	G34718	3.2	1.15	30	45	<5	0.99	3	22	56	2648	3.52	20	0.65	203	202	0.04	10	480	62	10	<20	59	0.04	<10	47	<10	5	267
29	G34719	1.0	0.32	85	35	5	1.51	2	15	61	249	4.49	<10	0.24	624	29	0.03	8	1260	40	30	<20	167	0.02	<10	23	<10	3	34
30	G34720	0.8	0.29	60	30	15	0.94	1	14	65	117	3.85	<10	0.18	306	14	0.05	6	1280	26	10	<20	113	0.02	<10	20	<10	2	15
31	G34721	0.7	0.28	30	30	5	1.27	<1	16	54	142	3.91	<10	0.36	520	36	0.03	9	1250	26	10	<20	177	0.02	<10	19	<10	3	24
32	G34722	0.9	0.28	10	30	<5	1.90	1	14	64	222	3.45	<10	0.47	829	14	0.04	6	1250	32	10	<20	252	0.02	<10	20	<10	3	33
33	G34723	0.4	0.33	<5	30	10	1.72	2	14	56	64	3.19	<10	0.45	728	24	0.04	7	1390	18	<5	<20	201	0.02	<10	19	<10	3	24
34	G34724	1.1	0.29	15	25	10	1.95	1	14	57	164	3.43	<10	0.47	831	75	0.04	7	1300	36	10	<20	257	0.02	<10	18	<10	3	32
35	G34725	1.5	0.31	10	30	20	2.05	13	13	51	134	3.06	<10	0.42	814	24	0.04	4	1280	146	10	<20	237	0.02	<10	16	<10	2	453
QC DATA:																													
Repeat:																													
1	G34691	2.2	0.34	<5	50	<5	1.31	3	26	49	2662	6.33	<10	0.47	634	10	0.02	10	2240	24	<5	<20	172	0.01	20	63	<10	4	41
10	G34700	0.5	0.39	<5	390	10	2.80	<1	11	53	80	2.69	<10	0.83	1278	4	0.02	5	920	12	10	<20	192	0.02	<10	27	<10	4	45
19	G34709	2.2	0.20	75	45	<5	3.00	<1	7	120	941	1.87	<10	0.29	1223	3	0.01	8	280	18	45	<20	250	0.02	<10	38	<10	2	25
Resplit:																													
1	G34691	2.1	0.36	<5	55	<5	1.36	2	29	41	2920	6.50	<10	0.46	648	8	0.02	10	2360	24	<5	<20	181	0.03	<10	63	<10	6	41
Standard:																													
Pb113		11.1	0.25	40	55	<5	1.72	39	3	5	2210	1.08	<10	0.11	1506	66	0.02	3	80	5542	20	<20	91	0.01	<10	8	70	<1	6904

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
df/7133
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5501

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

29-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07049
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34726	0.31	0.009
2	G34727	0.12	0.003
3	G34728	0.28	0.008
4	G34729	0.21	0.006
5	G34730	0.24	0.007
6	G34731	0.20	0.006
7	G34732	0.10	0.003
8	G34733	0.07	0.002
9	G34734	0.05	0.001
10	G34735	0.06	0.002
11	G34736	0.04	0.001
12	G34737	0.05	0.001
13	G34738	0.04	0.001
14	G34739	0.20	0.006
15	G34740	0.22	0.006
16	G34741	0.31	0.009
17	G34742	0.42	0.012
18	G34743	0.56	0.016
19	G34744	0.27	0.008
20	G34745	0.11	0.003
21	G34746	0.42	0.012
22	G34747	0.49	0.014
23	G34748	0.30	0.009
24	G34749	<0.03	<0.001
25	G34750	1.03	0.030
26	G34751	0.29	0.008

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 29-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	G34752	0.24	0.007
28	G34753	0.12	0.003
29	G34754	0.08	0.002
30	G34755	0.10	0.003
31	G34756	0.09	0.003
32	G34757	0.07	0.002
33	G34758	0.17	0.005
34	G34759	0.14	0.004
35	G34760	0.68	0.020

QC DATA:

Repeat:

1	G34726	0.29	0.008
10	G34735	0.06	0.002
19	G34744	0.26	0.008

Resplits:

1	G34726	0.34	0.010

Standard:

OXi54		1.88	0.055

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

22-A 07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5501

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07049
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34726	1.5	0.29	25	20	10	2.15	1	11	57	237	4.08	<10	0.49	1037	20	0.03	3	1190	86	25	<20	222	<0.01	<10	12	<10	4	64
2	G34727	0.7	0.25	20	25	5	1.14	<1	9	59	62	2.75	<10	0.18	388	19	0.05	4	1190	22	15	<20	146	<0.01	<10	18	<10	6	13
3	G34728	3.7	0.23	25	25	20	2.73	2	8	62	170	2.89	<10	0.20	928	181	0.03	4	1230	230	25	<20	268	<0.01	<10	14	<10	5	82
4	G34729	2.5	0.22	20	25	20	4.33	<1	14	43	90	2.98	<10	0.33	1749	33	0.03	7	1130	166	10	<20	375	<0.01	<10	12	<10	6	22
5	G34730	1.2	0.22	20	25	10	2.07	<1	9	57	68	3.42	<10	0.53	956	11	0.05	21	760	18	<5	<20	213	<0.01	<10	11	<10	4	25
6	G34731	1.6	0.28	20	25	5	2.42	<1	10	52	232	3.71	<10	0.63	1155	17	0.03	19	1220	26	15	<20	259	<0.01	<10	13	<10	6	57
7	G34732	1.6	0.23	35	20	<5	3.83	<1	8	52	274	2.40	<10	0.20	1361	18	0.04	4	1180	24	40	<20	296	<0.01	<10	12	<10	9	30
8	G34733	0.7	0.25	25	20	5	2.80	<1	10	45	267	2.79	<10	0.18	947	22	0.03	4	1250	18	15	<20	253	<0.01	<10	11	<10	7	13
9	G34734	3.4	0.22	70	20	<5	2.26	2	13	46	486	3.05	<10	0.17	779	69	0.03	5	1260	44	65	<20	227	<0.01	<10	11	<10	8	48
10	G34735	2.4	0.23	30	25	<5	2.53	1	11	41	447	3.34	<10	0.34	982	32	0.04	4	1260	34	30	<20	237	<0.01	<10	10	<10	7	39
11	G34736	1.0	0.26	25	20	5	1.23	<1	10	48	279	3.29	<10	0.27	499	17	0.05	4	1410	26	20	<20	134	<0.01	<10	11	<10	6	31
12	G34737	1.7	0.30	30	20	<5	1.54	1	12	46	457	4.30	<10	0.45	938	102	0.03	5	1450	22	35	<20	154	<0.01	<10	13	<10	7	49
13	G34738	2.7	0.29	45	25	<5	1.44	1	10	53	662	3.78	<10	0.46	818	157	0.04	4	1310	16	95	<20	119	<0.01	<10	14	<10	6	83
14	G34739	1.9	0.27	25	25	15	2.17	<1	13	56	53	4.08	<10	0.87	809	9	0.05	29	940	90	5	<20	265	<0.01	<10	11	<10	4	39
15	G34740	1.8	0.34	35	25	10	2.11	<1	14	51	104	3.58	<10	0.92	587	7	0.05	31	1720	38	<5	<20	375	<0.01	<10	15	<10	6	34
16	G34741	1.7	0.26	60	20	20	1.52	<1	13	46	25	5.41	<10	0.60	546	6	0.04	11	1340	42	<5	<20	233	<0.01	<10	13	<10	5	16
17	G34742	2.2	0.31	30	25	15	2.11	<1	10	45	320	5.44	<10	0.78	918	5	0.03	4	1670	36	<5	<20	298	<0.01	<10	17	<10	6	39
18	G34743	2.2	0.26	50	25	25	2.25	<1	27	54	100	5.44	<10	0.93	672	7	0.06	28	1060	22	5	<20	317	<0.01	<10	11	<10	4	27
19	G34744	1.3	0.30	50	30	10	2.22	<1	29	54	221	3.39	<10	0.94	705	5	0.05	45	1180	12	5	<20	277	<0.01	<10	14	<10	5	28
20	G34745	1.0	0.25	10	40	5	2.49	<1	6	61	66	2.50	<10	1.03	1113	4	0.07	16	840	12	<5	<20	270	<0.01	<10	17	<10	5	24
21	G34746	2.8	0.31	20	25	15	2.48	<1	14	58	48	3.66	<10	1.03	1292	8	0.06	43	1110	32	<5	<20	219	<0.01	<10	19	<10	5	40
22	G34747	4.3	0.28	25	20	20	1.82	<1	17	53	111	4.04	<10	0.77	1082	34	0.06	46	960	148	<5	<20	134	<0.01	<10	23	<10	4	57
23	G34748	1.6	0.35	25	30	10	2.85	<1	8	46	42	3.13	<10	1.20	1396	11	0.04	23	1120	50	<5	<20	242	<0.01	<10	16	<10	6	46
24	G34749	<0.2	1.03	5	230	<5	0.58	<1	7	92	8	2.21	<10	0.60	543	2	0.11	7	880	10	<5	<20	87	0.13	<10	40	<10	4	40
25	G34750	3.5	1.06	60	55	<5	0.70	3	15	53	3347	3.82	20	0.54	277	196	0.03	16	370	120	25	<20	40	0.03	<10	35	<10	8	144

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34751	1.4	0.31	25	25	10	2.36	<1	11	53	48	3.30	<10	0.95	1191	7	0.07	24	1000	40	<5	<20	135	<0.01	<10	18	<10	5	38
27	G34752	1.7	0.33	35	25	5	3.18	<1	10	49	165	2.69	<10	0.54	1552	22	0.02	19	1080	94	5	<20	196	<0.01	<10	16	<10	6	66
28	G34753	0.6	0.23	15	170	<5	2.82	<1	8	91	466	3.79	<10	0.90	999	3	0.02	6	310	8	10	<20	235	<0.01	<10	104	<10	2	48
29	G34754	1.9	0.34	25	20	15	2.04	<1	8	57	181	3.78	<10	0.47	1238	41	0.01	7	1290	182	<5	<20	171	<0.01	<10	20	<10	5	33
30	G34755	1.1	0.28	40	15	10	2.26	<1	12	50	114	3.77	<10	0.32	1699	47	0.02	5	1160	66	5	<20	278	<0.01	<10	10	<10	7	55
31	G34756	0.6	0.28	50	25	10	3.68	<1	14	49	70	3.18	<10	0.54	1767	12	0.03	4	1270	50	<5	<20	295	<0.01	<10	9	<10	7	28
32	G34757	0.8	0.29	30	40	<5	3.41	<1	10	43	152	2.31	<10	0.60	1575	2	0.03	3	1210	18	15	<20	277	<0.01	<10	9	<10	5	43
33	G34758	0.9	0.30	50	30	<5	2.99	<1	17	43	155	2.74	<10	0.53	1553	5	0.03	4	1230	68	10	<20	256	<0.01	<10	9	<10	6	46
34	G34759	1.1	0.29	45	20	5	2.36	2	12	45	100	3.83	<10	0.77	1698	12	0.03	4	1260	262	<5	<20	188	<0.01	<10	9	<10	5	134
35	G34760	1.8	0.28	25	30	<5	2.67	2	10	59	965	2.94	<10	0.88	1046	18	0.03	13	1110	56	15	<20	197	<0.01	<10	11	<10	5	121
QC DATA:																													
Repeat:																													
1	G34726	1.7	0.27	25	20	10	2.13	1	11	58	238	4.09	<10	0.48	1035	19	0.03	3	1180	86	25	<20	224	<0.01	<10	12	<10	4	65
10	G34735	2.3	0.22	30	25	<5	2.50	1	11	41	435	3.31	<10	0.33	1007	31	0.05	4	1300	32	30	<20	232	<0.01	<10	11	<10	7	36
19	G34744	1.4	0.28	50	25	10	2.11	<1	30	52	220	3.38	<10	0.95	703	5	0.05	45	1190	12	5	<20	276	<0.01	<10	15	<10	5	28
Resplit:																													
1	G34726	1.5	0.29	25	20	10	2.28	<1	12	64	220	3.96	<10	0.49	1030	20	0.04	3	1220	56	15	<20	230	<0.01	<10	12	<10	4	68
Standard:																													
Pb113		11.2	0.25	55	45	<5	1.62	37	2	<1	2197	1.08	<10	0.11	1468	65	0.02	1	90	5368	10	<20	80	0.01	<10	5	<10	1	6929

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/n5496
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5502

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

24-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07050
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34761	0.36	0.010
2	G34762	0.52	0.015
3	G34763	0.34	0.010
4	G34764	0.42	0.012
5	G34765	0.32	0.009
6	G34766	0.26	0.008
7	G34767	0.10	0.003
8	G34768	0.31	0.009
9	G34769	0.07	0.002
10	G34770	0.13	0.004
11	G34771	<0.03	<0.001
12	G34772	0.06	0.002
13	G34773	<0.03	<0.001
14	G34774	0.05	0.001
15	G34775	0.19	0.006
16	G34776	0.37	0.011
17	G34777	0.32	0.009
18	G34778	0.08	0.002
19	G34779	0.09	0.003
20	G34780	0.05	0.001
21	G34781	<0.03	<0.001
22	G34782	0.25	0.007
23	G34783	0.15	0.004
24	G34784	0.13	0.004
25	G34785	0.06	0.002
26	G34786	0.28	0.008
27	G34787	0.40	0.012

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5502 24-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G34788	0.22	0.006
29	G34789	0.16	0.005
30	G34790	0.07	0.002
31	G34791	0.16	0.005
32	G34792	0.09	0.003
33	G34793	0.08	0.002
34	G34794	0.13	0.004
35	G34795	1.88	0.055

QC DATA:

Resplits:

1	G34761	0.40	0.012

Standard:

SI25		1.80	0.052

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

22-A

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5502

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07050
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34761	0.9	0.43	10	140	<5	3.11	3	9	55	657	3.06	<10	1.03	1008	18	0.01	15	1140	14	10	<20	195	0.02	<10	15	<10	5	80
2	G34762	1.1	0.45	10	85	<5	2.34	1	15	47	1095	3.31	<10	0.90	986	17	0.02	15	1260	16	5	<20	107	0.02	<10	17	<10	4	60
3	G34763	0.5	0.84	<5	65	<5	1.91	2	15	31	512	3.77	<10	1.07	719	12	0.03	26	1660	20	<5	<20	145	0.02	<10	21	<10	4	72
4	G34764	1.6	0.51	70	40	<5	3.04	3	15	55	627	3.71	<10	1.21	1471	12	0.02	29	1320	74	15	<20	229	0.03	<10	20	<10	6	102
5	G34765	1.7	0.38	70	40	<5	2.38	<1	18	59	1203	3.39	<10	0.82	1030	51	0.03	26	1390	224	10	<20	144	0.02	<10	18	<10	8	35
6	G34766	1.0	0.32	60	55	<5	1.70	<1	11	103	693	1.82	20	0.59	675	234	0.05	16	720	106	10	<20	112	0.01	<10	18	<10	5	32
7	G34767	0.3	0.60	35	80	<5	1.50	<1	11	81	495	1.67	20	0.79	585	55	0.06	21	1200	22	10	<20	118	0.02	<10	37	<10	7	29
8	G34768	1.0	0.67	40	50	<5	2.16	<1	24	79	2120	2.49	<10	0.80	817	47	0.06	23	580	24	5	<20	171	0.01	<10	39	<10	6	23
9	G34769	0.4	1.17	30	65	<5	1.85	<1	19	59	136	2.29	10	1.20	647	7	0.07	27	1670	38	10	<20	134	0.02	<10	76	<10	8	57
10	G34770	0.4	1.87	<5	65	<5	2.89	2	31	59	762	5.79	10	1.91	877	35	0.04	30	1390	42	15	<20	251	0.03	<10	89	<10	7	53
11	G34771	0.2	1.32	15	155	10	1.78	<1	12	53	137	2.57	20	1.25	496	5	0.06	25	1180	26	<5	<20	152	0.02	<10	70	<10	8	25
12	G34772	<0.2	1.51	20	95	<5	2.00	<1	19	108	419	4.05	10	1.46	777	12	0.06	68	1320	30	5	<20	175	0.05	<10	122	<10	9	31
13	G34773	<0.2	1.02	10	250	20	0.52	<1	8	97	5	2.21	<10	0.60	551	3	0.10	8	940	20	<5	<20	94	0.10	<10	47	<10	2	41
14	G34774	<0.2	0.98	15	75	<5	1.71	<1	13	156	250	2.61	10	0.87	588	9	0.08	53	1030	22	<5	<20	150	0.02	<10	94	<10	6	23
15	G34775	0.3	0.95	20	70	<5	2.05	2	16	106	658	3.14	<10	0.82	771	36	0.06	33	510	36	<5	<20	181	0.02	<10	75	<10	2	31
16	G34776	0.9	1.16	90	50	<5	2.43	2	14	84	447	4.06	<10	1.00	1030	6	0.04	25	600	68	5	<20	216	0.03	<10	66	<10	2	61
17	G34777	0.9	1.07	70	50	<5	2.37	3	13	96	401	3.72	<10	0.93	998	10	0.05	28	620	62	20	<20	211	0.02	<10	64	<10	2	57
18	G34778	0.4	1.04	20	85	<5	1.26	<1	16	58	375	1.81	10	0.94	425	19	0.05	25	950	26	<5	<20	106	0.03	<10	71	<10	7	23
19	G34779	0.2	1.33	10	150	<5	1.64	<1	14	77	458	2.65	<10	1.36	553	17	0.07	23	800	30	10	<20	193	0.04	<10	90	<10	5	20
20	G34780	<0.2	1.18	10	75	<5	1.55	<1	19	62	299	2.24	10	1.18	391	11	0.08	23	1500	26	10	<20	144	0.04	<10	83	<10	8	22
21	G34781	0.3	1.18	25	75	<5	1.27	<1	18	58	154	1.72	20	1.17	338	7	0.07	32	1600	26	10	<20	105	0.06	<10	71	<10	10	20
22	G34782	0.4	1.37	15	70	<5	2.17	<1	35	57	1221	3.42	10	1.15	700	22	0.05	33	1340	36	<5	<20	212	0.05	<10	70	<10	7	26
23	G34783	0.5	2.41	35	70	<5	4.84	1	29	33	965	5.32	10	2.21	2924	17	0.02	35	1650	40	15	<20	411	0.06	<10	66	<10	9	51
24	G34784	0.4	1.81	40	70	<5	2.82	<1	24	31	702	3.11	<10	1.57	1775	17	0.02	30	1770	34	20	<20	233	0.04	<10	45	<10	12	41
25	G34785	0.3	1.43	35	75	<5	2.19	<1	12	30	369	1.92	<10	1.01	1109	14	0.02	22	2100	30	15	<20	194	0.03	<10	35	<10	14	27

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34786	0.6	1.10	30	65	<5	2.29	<1	19	27	476	1.56	<10	0.69	980	10	0.02	24	1610	26	10	<20	208	0.03	<10	31	<10	13	16
27	G34787	0.4	1.49	<5	55	<5	2.84	1	23	62	760	4.36	20	1.27	1258	10	0.04	52	1510	26	10	<20	240	0.05	<10	72	<10	8	29
28	G34788	0.3	1.36	35	60	<5	1.98	<1	29	119	379	3.27	<10	1.49	732	12	0.07	92	1320	34	10	<20	188	0.07	<10	107	<10	7	24
29	G34789	<0.2	1.71	10	75	<5	3.92	1	20	69	421	4.59	20	1.61	1659	10	0.03	45	1680	32	10	<20	387	0.05	<10	84	<10	7	43
30	G34790	0.2	1.39	15	70	<5	1.71	<1	18	86	410	2.89	<10	1.27	700	13	0.06	52	1310	32	<5	<20	156	0.06	<10	71	<10	8	28
31	G34791	0.3	1.09	15	65	<5	2.44	<1	17	158	899	3.16	<10	1.01	1008	14	0.07	65	1200	26	<5	<20	213	0.04	<10	87	<10	6	27
32	G34792	0.3	1.70	15	60	<5	3.61	1	22	193	402	5.33	<10	1.73	1770	16	0.04	81	990	42	15	<20	327	0.05	<10	118	<10	2	59
33	G34793	0.2	0.87	10	60	<5	2.11	<1	14	103	409	2.50	<10	0.68	853	21	0.05	40	890	26	<5	<20	217	0.04	<10	58	<10	5	19
34	G34794	0.2	0.71	25	65	<5	1.51	<1	18	85	623	2.20	<10	0.50	653	25	0.07	35	930	24	<5	<20	164	0.05	<10	63	<10	6	15
35	G34795	4.0	1.11	45	40	<5	1.06	2	24	58	8575	4.18	10	0.63	214	609	0.04	65	230	70	25	<20	64	0.02	<10	45	<10	6	74
QC DATA:																													
Repeat:																													
1	G34761	1.0	0.43	20	135	<5	3.11	2	9	55	665	3.07	<10	1.04	1010	16	0.02	13	1120	12	5	<20	192	0.02	<10	15	<10	4	80
10	G34770	0.4	1.83	5	70	<5	3.01	3	31	69	763	5.82	10	2.18	832	33	0.04	30	1340	48	20	<20	253	0.04	<10	86	<10	8	52
19	G34779	0.2	1.31	15	155	<5	1.63	1	14	78	443	2.63	<10	1.33	547	19	0.07	24	800	30	20	<20	185	0.03	20	91	<10	4	21
Resplit:																													
1	G34761	0.9	0.45	15	155	<5	3.43	3	9	51	718	3.24	<10	1.13	1016	20	0.02	17	1170	14	15	<20	206	0.02	<10	15	<10	5	88
Standard:																													
Pb113		11.7	0.26	55	60	<5	1.73	44	3	6	2275	1.08	<10	0.11	1494	68	0.02	4	90	547	20	<20	73	0.01	<10	8	10	<1	6937

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
df/7133
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5503

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

29-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07051
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34796	0.14	0.004
2	G34797	0.08	0.002
3	G34798	0.17	0.005
4	G34799	0.05	0.001
5	G34800	0.41	0.012
6	G34801	0.35	0.010
7	G34802	14.7	0.429
8	G34803	0.78	0.023
9	G34804	1.69	0.049
10	G34805	0.10	0.003
11	G34806	0.57	0.017
12	G34807	0.27	0.008
13	G34808	0.25	0.007
14	G34809	0.22	0.006
15	G34810	0.42	0.012
16	G34811	0.10	0.003
17	G34812	0.34	0.010
18	G34813	0.30	0.009
19	G34814	0.54	0.016
20	G34815	3.60	0.105
21	G34816	0.34	0.010
22	G34817	0.68	0.020
23	G34818	0.60	0.017
24	G34819	0.20	0.006
25	G34820	1.25	0.036
26	G34821	1.02	0.030
27	G34822	1.29	0.038

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AK7-5503 29-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G34823	0.68	0.020
29	G34824	0.40	0.012
30	G34825	0.28	0.008
31	G34826	0.26	0.008
32	G34827	0.30	0.009
33	G34828	0.55	0.016
34	G34829	<0.03	<0.001
35	G34830	0.38	0.011

QC DATA:

Repeat:

1	G34796	0.14	0.004
7	G34802	15.8	0.461
9	G34804	1.77	0.052
10	G34805	0.11	0.003
19	G34814	0.43	0.013
20	G34815	3.59	0.105

Resplits:

1	G34796	0.15	0.004

Standard:

Oxi54		1.83	0.053

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

23-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 2007- 5503

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07051
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34796	0.3	0.71	10	95	<5	2.00	<1	13	74	354	2.00	<10	0.49	827	21	0.07	23	830	20	<5	<20	176	0.04	<10	60	<10	4	13
2	G34797	0.2	0.75	<5	125	<5	2.21	<1	10	83	414	2.00	<10	0.58	1015	9	0.08	10	470	22	<5	<20	228	0.04	<10	43	<10	3	14
3	G34798	0.2	0.71	<5	105	<5	1.73	<1	10	79	401	1.92	<10	0.48	732	5	0.07	11	550	24	<5	<20	189	0.04	<10	42	<10	5	15
4	G34799	<0.2	0.85	<5	115	<5	1.57	<1	9	96	261	2.22	<10	0.61	706	5	0.06	9	550	26	<5	<20	166	0.06	<10	48	<10	4	30
5	G34800	0.6	1.02	30	40	<5	2.48	<1	20	70	1076	3.63	<10	0.78	920	15	0.04	28	880	82	10	<20	217	0.06	<10	56	<10	7	27
6	G34801	0.2	1.00	50	60	<5	3.62	<1	19	73	379	2.19	10	0.83	1222	8	0.07	26	1090	26	<5	<20	232	0.07	<10	65	<10	10	17
7	G34802	1.0	1.43	105	45	<5	2.38	2	34	75	1104	4.77	<10	1.27	981	14	0.04	70	1600	34	15	<20	176	0.06	<10	96	<10	10	29
8	G34803	0.2	1.15	75	40	<5	1.99	<1	25	59	577	3.25	<10	0.81	757	25	0.06	29	1190	32	<5	<20	170	0.05	<10	52	<10	8	23
9	G34804	0.4	1.28	135	45	<5	3.11	2	20	54	578	4.42	<10	1.02	1240	26	0.04	26	870	40	20	<20	265	0.05	<10	38	<10	6	29
10	G34805	0.2	1.28	20	85	<5	1.59	<1	17	89	415	2.71	10	1.17	532	14	0.11	33	1180	30	<5	<20	128	0.09	<10	79	<10	8	24
11	G34806	0.5	1.22	20	55	<5	1.56	<1	22	69	1008	3.37	10	1.07	599	31	0.08	29	1080	38	15	<20	126	0.07	<10	78	<10	9	30
12	G34807	0.4	1.29	15	80	<5	1.95	<1	17	62	1344	2.77	10	1.12	686	11	0.06	19	1530	48	<5	<20	148	0.08	<10	73	<10	9	46
13	G34808	0.5	1.68	10	35	<5	2.94	<1	17	59	372	3.78	<10	1.96	1465	12	0.07	18	1220	78	<5	<20	521	0.15	<10	88	<10	7	164
14	G34809	0.5	2.55	30	45	<5	3.15	<1	28	76	375	5.64	<10	3.19	2172	14	0.10	43	1250	58	20	<20	561	0.20	<10	134	<10	7	278
15	G34810	0.8	2.32	35	55	<5	2.84	2	21	55	472	4.70	<10	2.58	1697	31	0.05	48	1440	54	35	<20	244	0.10	<10	93	<10	9	132
16	G34811	0.3	1.49	20	60	<5	2.07	<1	18	54	314	3.22	<10	1.34	904	32	0.07	22	1660	36	<5	<20	154	0.09	<10	64	<10	12	36
17	G34812	0.7	1.62	20	55	<5	1.89	<1	19	52	994	3.62	<10	1.40	821	23	0.06	31	2120	40	10	<20	124	0.08	<10	76	<10	11	44
18	G34813	0.6	1.88	35	65	<5	3.02	1	19	55	527	4.54	<10	1.73	1155	25	0.06	48	2830	72	20	<20	189	0.10	<10	86	<10	10	164
19	G34814	0.6	1.90	20	50	<5	6.06	1	28	46	756	4.86	<10	1.98	2877	38	0.03	32	1070	48	20	<20	363	0.10	<10	82	<10	7	74
20	G34815	0.8	1.66	20	60	<5	7.53	1	15	48	596	3.91	<10	2.03	2760	79	0.04	13	710	54	15	<20	454	0.11	<10	100	<10	5	57
21	G34816	0.6	1.43	25	45	<5	4.74	<1	11	59	525	4.02	<10	1.43	2174	118	0.05	17	890	46	<5	<20	272	0.10	<10	64	<10	8	72
22	G34817	0.7	1.62	40	45	<5	4.55	1	22	72	297	4.74	<10	1.57	2932	38	0.03	61	1270	64	10	<20	242	0.11	<10	59	<10	6	111
23	G34818	0.9	1.90	60	50	<5	5.17	<1	24	48	313	5.17	<10	1.93	3558	13	0.02	65	1240	70	15	<20	245	0.13	<10	60	<10	8	105
24	G34819	0.7	1.79	40	65	<5	3.13	<1	18	64	540	4.92	<10	1.61	1985	9	0.04	41	1380	50	<5	<20	118	0.14	<10	54	<10	11	75
25	G34820	1.2	2.03	25	60	<5	3.24	2	33	64	1724	6.90	<10	1.77	2201	17	0.01	49	1350	66	20	<20	113	0.14	<10	73	<10	9	97

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007- 5503 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34821	1.1	1.41	30	45	<5	3.24	<1	21	84	959	5.77	<10	1.24	1954	61	0.03	23	910	58	<5	<20	99	0.15	<10	73	<10	5	76
27	G34822	2.5	2.27	50	75	<5	4.17	3	28	56	1699	8.08	<10	2.67	3938	30	0.02	32	890	100	20	<20	156	0.15	<10	119	<10	4	408
28	G34823	1.2	2.47	40	65	<5	4.15	<1	15	56	644	6.23	<10	3.00	3152	56	0.05	24	1110	114	15	<20	191	0.17	<10	110	<10	4	281
29	G34824	0.3	2.44	45	105	<5	3.86	2	11	67	183	5.40	<10	2.59	2678	14	0.14	24	1170	84	35	<20	251	0.14	<10	121	<10	4	144
30	G34825	3.2	1.26	50	45	<5	1.05	<1	23	60	2659	3.63	20	0.65	210	196	0.04	4	540	66	<5	<20	63	0.08	<10	49	<10	8	277
31	G34826	0.4	3.15	50	140	15	3.68	<1	12	60	149	4.95	<10	3.86	2626	14	0.06	41	1790	90	20	<20	320	0.19	<10	95	<10	7	122
32	G34827	1.3	2.98	45	115	20	3.22	1	16	71	257	5.28	<10	3.73	2434	35	0.11	46	1380	116	30	<20	198	0.19	<10	110	<10	6	157
33	G34828	2.2	2.41	50	80	<5	6.23	2	18	64	410	5.93	<10	2.36	3245	41	0.03	48	1280	112	30	<20	213	0.18	<10	97	<10	7	198
34	G34829	<0.2	1.15	50	265	35	0.70	<1	9	100	6	2.31	<10	0.61	576	<1	0.11	4	970	22	<5	<20	88	0.15	<10	50	<10	5	44
35	G34830	0.4	1.33	50	65	<5	2.42	1	20	72	306	3.89	<10	1.16	1151	15	0.08	23	1510	104	20	<20	119	0.11	<10	68	<10	11	64
QC DATA:																													
Repeat:																													
1	G34796	0.3	0.74	15	100	<5	2.03	<1	13	77	360	2.05	<10	0.50	841	19	0.07	21	860	22	<5	<20	189	0.06	<10	62	<10	7	14
10	G34805	0.2	1.27	25	80	<5	1.61	<1	17	89	407	2.74	10	1.14	536	12	0.10	32	1220	32	<5	<20	130	0.09	<10	80	<10	7	25
19	G34814	0.7	1.94	20	40	<5	6.20	<1	29	48	750	4.97	<10	1.95	2918	38	0.03	32	1120	52	<5	<20	360	0.12	<10	86	<10	6	78
Resplit:																													
1	G34796	0.3	0.78	10	95	<5	2.04	<1	14	71	379	2.19	<10	0.48	845	21	0.07	26	800	24	<5	<20	175	0.05	<10	61	<10	6	15
Standard:																													
Pb113		11.8	0.24	45	55	<5	1.65	40	4	7	2218	1.14	<10	0.10	1551	69	0.02	2	100	5676	25	<20	85	0.02	<10	9	<10	<1	7029

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5503S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5504

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

20-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07052
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34831	0.23	0.007
2	G34832	0.08	0.002
3	G34833	0.09	0.003
4	G34834	0.21	0.006
5	G34835	0.42	0.012
6	G34836	0.22	0.006
7	G34837	0.21	0.006
8	G34838	0.30	0.009
9	G34839	5.77	0.168
10	G34840	0.61	0.018
11	G34841	0.37	0.011
12	G34842	0.24	0.007
13	G34843	0.75	0.022
14	G34844	0.76	0.022
15	G34845	0.99	0.029
16	G34846	0.39	0.011
17	G34847	0.26	0.008
18	G34848	0.35	0.010
19	G34849	0.28	0.008
20	G34850	0.28	0.008
21	G34851	0.12	0.003
22	G34852	0.13	0.004
23	G34853	0.19	0.006
24	G34854	0.19	0.006
25	G34855	0.18	0.005
26	G34856	0.14	0.004
27	G34857	0.16	0.005

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5504 20-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G34858	0.12	0.003
29	G34859	0.16	0.005
30	G34860	0.10	0.003
31	G34861	0.31	0.009
32	G34862	0.26	0.008
33	G34863	0.27	0.008
34	G34864	<0.03	<0.001
35	G34865	0.26	0.008

QC DATA:

Repeat:

1	G34831	0.19	0.006
5	G34835	0.40	0.012
6	G34836	0.21	0.006
9	G34839	5.61	0.164
10	G34840	0.56	0.016
13	G34843	0.77	0.022
14	G34844	0.70	0.020
19	G34849	0.24	0.007

Resplits:

1	G34831	0.18	0.005

Standard:

SI25		1.78	0.052
SI25		1.81	0.053

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5504

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07052
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34831	0.3	0.84	20	50	<5	1.99	<1	12	78	330	3.24	<10	0.59	984	10	0.05	18	1000	26	<5	<20	126	0.07	<10	46	<10	9	30
2	G34832	0.4	1.03	20	60	<5	1.30	<1	10	64	352	2.55	<10	0.72	829	11	0.06	25	1100	20	<5	<20	95	0.07	<10	65	<10	11	39
3	G34833	0.3	0.95	30	50	<5	1.85	1	15	67	393	3.86	10	0.62	984	4	0.05	25	1620	16	<5	<20	129	0.06	<10	49	<10	14	42
4	G34834	0.4	0.90	35	45	<5	1.90	1	16	74	468	4.90	<10	0.57	1057	14	0.05	25	1150	34	<5	<20	153	0.03	<10	41	<10	9	45
5	G34835	0.8	1.39	40	60	<5	2.10	2	13	66	403	6.16	<10	1.02	1479	15	0.05	30	1570	70	<5	<20	158	0.05	<10	49	<10	10	86
6	G34836	0.5	1.40	25	55	<5	1.58	2	12	87	517	5.83	<10	1.06	1270	6	0.06	16	860	108	<5	<20	121	0.02	<10	52	<10	6	100
7	G34837	0.9	1.50	30	55	<5	2.12	2	14	67	456	5.96	<10	1.23	1616	10	0.06	25	1190	190	<5	<20	156	0.03	<10	58	<10	8	130
8	G34838	1.6	1.90	35	70	<5	3.58	2	12	78	316	6.00	10	1.84	2484	15	0.05	64	1440	178	<5	<20	235	0.07	<10	81	<10	11	167
9	G34839	3.8	2.17	35	80	120	3.69	2	13	62	571	5.90	<10	2.21	2520	19	0.05	31	1080	74	<5	<20	268	0.06	<10	82	<10	9	151
10	G34840	1.0	2.10	40	70	<5	2.39	2	20	60	1252	8.25	<10	2.06	2228	19	0.04	19	1290	56	<5	<20	236	0.08	<10	74	<10	9	138
11	G34841	0.8	2.04	40	70	<5	2.49	2	24	64	435	6.75	<10	2.50	1931	28	0.05	28	1300	56	<5	<20	225	0.11	<10	127	<10	10	141
12	G34842	0.4	2.46	40	105	<5	2.54	2	27	79	325	6.53	<10	2.84	2019	18	0.32	29	1120	44	<5	<20	215	0.18	<10	146	<10	10	153
13	G34843	0.5	2.73	35	320	<5	6.94	2	21	50	279	6.92	<10	3.42	4136	31	0.10	21	850	56	<5	<20	457	0.15	<10	161	<10	10	168
14	G34844	1.4	2.22	35	260	10	3.17	3	39	65	629	8.68	<10	2.77	2573	25	0.15	21	1010	126	<5	<20	295	0.11	<10	145	<10	7	181
15	G34845	3.6	1.18	60	65	<5	0.71	4	16	60	3283	3.81	20	0.57	227	238	0.03	19	350	130	40	<20	44	0.04	<10	42	<10	9	169
16	G34846	0.9	2.10	40	465	5	3.22	2	10	68	210	7.02	<10	2.75	3120	19	0.10	11	720	88	<5	<20	453	0.10	<10	121	<10	6	97
17	G34847	0.4	2.44	35	360	<5	5.86	2	9	67	248	5.66	<10	3.16	4153	50	0.10	18	740	30	<5	<20	590	0.11	<10	148	<10	7	165
18	G34848	0.7	2.27	50	200	<5	2.61	2	8	76	376	7.82	<10	2.60	2675	28	0.22	23	830	34	<5	<20	269	0.09	<10	105	<10	6	164
19	G34849	0.7	2.26	45	110	<5	3.76	2	10	73	168	6.06	<10	2.72	2354	15	0.10	34	950	42	<5	<20	332	0.07	<10	116	<10	7	167
20	G34850	2.8	0.97	30	45	<5	2.05	3	15	74	1004	4.80	<10	0.85	1625	12	0.03	10	1090	84	<5	<20	228	<0.01	<10	63	<10	4	176
21	G34851	0.9	1.29	55	185	<5	>10	<1	4	33	294	2.12	<10	3.49	4141	17	0.01	6	2070	42	<5	<20	610	0.02	<10	52	<10	5	64
22	G34852	1.2	1.47	40	95	<5	7.83	1	6	35	172	3.04	<10	4.11	4548	15	0.02	10	1090	72	10	<20	474	0.02	<10	46	<10	9	107
23	G34853	1.3	1.17	40	50	<5	2.44	1	14	41	617	4.08	<10	0.96	1563	29	0.02	13	1610	26	5	<20	188	<0.01	<10	35	<10	8	55
24	G34854	1.4	0.68	25	60	<5	2.38	1	11	71	392	2.66	<10	0.66	1727	16	0.04	20	840	142	<5	<20	203	<0.01	<10	24	<10	5	82
25	G34855	0.8	0.60	25	50	<5	2.06	1	8	71	356	3.22	<10	0.62	977	2	0.04	27	610	36	<5	<20	195	<0.01	<10	32	<10	4	87

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34856	0.5	0.44	25	55	<5	2.34	<1	7	83	170	2.66	<10	0.60	1073	3	0.04	20	590	22	<5	<20	228	<0.01	<10	21	<10	5	34
27	G34857	0.4	0.50	40	55	<5	1.66	<1	9	90	369	2.52	<10	0.53	666	7	0.05	22	700	18	<5	<20	182	<0.01	<10	29	<10	6	28
28	G34858	0.4	0.39	25	65	<5	1.74	<1	7	96	292	2.02	<10	0.41	672	6	0.05	16	680	20	<5	<20	187	<0.01	<10	18	<10	5	22
29	G34859	0.4	0.32	35	70	<5	2.82	<1	7	93	142	2.10	<10	0.54	1183	5	0.03	19	740	42	<5	<20	278	<0.01	<10	14	<10	6	34
30	G34860	0.5	0.29	30	60	<5	1.52	<1	7	100	150	2.52	<10	0.43	846	4	0.05	20	670	42	<5	<20	167	<0.01	<10	12	<10	4	44
31	G34861	0.5	0.24	35	55	<5	2.63	<1	7	89	177	2.74	<10	0.38	1155	3	0.04	17	580	32	<5	<20	228	<0.01	<10	11	<10	6	52
32	G34862	0.4	0.26	115	55	<5	1.89	<1	9	98	185	2.41	<10	0.39	954	4	0.04	17	600	36	<5	<20	194	<0.01	<10	12	<10	4	51
33	G34863	0.4	0.30	65	55	<5	1.82	<1	9	116	192	2.57	<10	0.38	874	6	0.05	19	650	34	<5	<20	182	<0.01	<10	13	<10	4	53
34	G34864	<0.2	1.23	10	325	<5	0.74	<1	8	179	2	2.65	10	0.56	722	<1	0.13	9	990	10	<5	<20	146	0.17	<10	45	<10	7	63
35	G34865	0.6	0.30	35	40	<5	1.38	1	13	111	625	2.98	<10	0.23	678	13	0.04	19	660	64	<5	<20	156	<0.01	<10	8	<10	4	46
QC DATA:																													
Repeat:																													
1	G34831	0.3	0.77	20	50	<5	1.99	<1	13	80	313	3.48	<10	0.56	969	10	0.04	18	1040	28	<5	<20	132	0.06	<10	45	<10	9	33
10	G34840	1.0	2.15	40	70	<5	2.93	3	21	62	1274	8.55	<10	2.06	2436	22	0.04	20	1350	60	<5	<20	251	0.08	<10	74	<10	8	153
19	G34849	0.8	2.32	45	100	<5	3.50	2	10	74	184	6.21	<10	2.85	2384	17	0.08	34	960	44	<5	<20	332	0.06	<10	119	<10	7	171
Resplit:																													
1	G34831	0.3	0.84	20	55	<5	1.95	<1	12	85	333	3.48	<10	0.57	910	11	0.04	20	1100	30	<5	<20	127	0.07	<10	48	<10	10	30
Standard:																													
Pb113		11.4	0.27	45	75	<5	1.66	51	2	1	2264	1.19	<10	0.10	1584	63	0.02	1	80	5456	<5	<20	87	0.01	<10	6	<10	8	7012

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
df/n5504
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5505

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

20-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07053
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36816	0.11	0.003
2	G36817	0.04	0.001
3	G36818	0.09	0.003
4	G36819	0.07	0.002
5	G36820	0.06	0.002
6	G36821	0.07	0.002
7	G36822	0.08	0.002
8	G36823	0.06	0.002
9	G36824	0.07	0.002
10	G36825	0.09	0.003
11	G36826	0.10	0.003
12	G36827	0.09	0.003
13	G36828	0.10	0.003
14	G36829	0.12	0.003
15	G36830	0.11	0.003
16	G36831	0.10	0.003
17	G36832	<0.03	<0.001
18	G36833	0.16	0.005
19	G36834	0.10	0.003
20	G36835	0.11	0.003
21	G36836	0.98	0.029
22	G36837	0.12	0.003
23	G36838	0.28	0.008
24	G36839	0.08	0.002
25	G36840	0.08	0.002
26	G36841	0.16	0.005
27	G36842	0.07	0.002
28	G36843	0.14	0.004

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5505 20-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G36844	1.30	0.038
30	G36845	0.86	0.025
31	G36846	0.81	0.024
32	G36847	0.75	0.022
33	G36848	0.84	0.024
34	G36849	0.82	0.024
35	G36850	1.09	0.032

QC DATA:

Repeat:

1	G36816	0.10	0.003
10	G36825	0.09	0.003
19	G36834	0.07	0.002
30	G36845	0.74	0.022
34	G36849	0.81	0.024
35	G36850	1.02	0.030

Resplits:

1	G36816	0.11	0.003

Standard:

Si25		1.78	0.052
Si25		1.79	0.052

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

22-/ 07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5505

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07053
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36816	1.1	0.55	45	50	<5	1.23	3	12	90	96	5.59	<10	0.39	654	3	0.02	3	1630	52	20	<20	76	<0.01	<10	11	<10	7	62
2	G36817	0.8	0.64	30	30	<5	0.84	2	12	59	64	5.22	<10	0.65	587	<1	0.03	3	1740	66	10	<20	61	0.01	<10	21	<10	7	42
3	G36818	0.8	0.60	30	35	<5	1.84	2	12	78	90	4.38	<10	0.56	986	1	0.02	4	1620	30	15	<20	120	0.02	<10	18	<10	8	40
4	G36819	1.1	0.71	40	30	<5	0.84	2	12	82	107	5.34	<10	0.68	465	<1	0.03	3	1780	26	20	<20	58	0.01	<10	20	<10	7	44
5	G36820	0.2	0.70	15	30	<5	1.08	1	14	87	23	5.39	<10	0.62	444	2	0.02	3	1830	20	<5	<20	67	0.02	<10	17	<10	7	23
6	G36821	<0.2	0.60	15	30	<5	1.05	1	12	59	22	5.30	<10	0.55	415	<1	0.02	3	1730	28	<5	<20	74	0.02	<10	11	<10	7	22
7	G36822	0.3	0.65	15	30	<5	1.18	1	14	82	64	5.56	<10	0.56	452	2	0.02	3	1740	24	<5	<20	75	0.04	<10	18	<10	7	29
8	G36823	0.3	0.66	20	35	<5	1.41	1	14	61	38	4.70	<10	0.57	529	<1	0.03	3	1720	30	<5	<20	83	0.05	<10	19	<10	8	29
9	G36824	0.2	0.77	10	35	<5	1.98	<1	15	46	56	4.56	<10	0.80	758	1	0.03	5	1690	12	<5	<20	110	0.10	<10	28	<10	10	33
10	G36825	0.2	0.95	15	40	<5	1.94	1	16	42	56	4.65	<10	0.94	761	<1	0.03	5	1810	12	<5	<20	97	0.10	<10	30	<10	8	39
11	G36826	0.4	0.84	10	40	<5	2.22	<1	17	45	74	4.66	<10	0.85	817	<1	0.03	5	1730	14	<5	<20	131	0.10	<10	31	<10	8	35
12	G36827	0.4	0.84	15	40	<5	2.61	1	18	38	61	4.95	<10	0.79	946	<1	0.03	5	1800	14	<5	<20	123	0.10	<10	30	<10	8	37
13	G36828	0.3	0.91	15	40	<5	1.90	1	15	50	54	5.12	<10	0.90	860	1	0.03	5	1670	14	<5	<20	107	0.09	<10	30	<10	7	51
14	G36829	0.4	0.65	20	35	<5	2.11	1	15	55	23	6.11	<10	0.55	770	<1	0.03	4	1560	28	<5	<20	100	0.08	<10	20	<10	8	33
15	G36830	0.2	0.63	15	40	<5	1.45	<1	16	54	50	4.94	<10	0.54	526	2	0.02	4	1580	24	<5	<20	151	0.06	<10	19	<10	8	36
16	G36831	0.3	0.67	15	40	<5	1.70	<1	15	63	57	4.85	<10	0.61	639	1	0.02	5	1590	20	<5	<20	79	0.06	<10	23	<10	8	36
17	G36832	<0.2	1.13	10	285	<5	0.57	<1	8	177	3	2.62	<10	0.59	687	2	0.11	9	1040	8	<5	<20	129	0.16	<10	45	<10	5	58
18	G36833	0.5	0.52	15	35	<5	1.58	1	16	66	95	5.35	<10	0.36	541	2	0.02	4	1500	28	<5	<20	103	0.03	<10	12	<10	7	36
19	G36834	0.4	0.56	15	60	<5	2.20	5	13	72	59	4.70	<10	0.42	743	1	0.01	4	1520	76	<5	<20	228	0.04	<10	15	<10	8	180
20	G36835	0.4	0.55	20	40	<5	2.71	2	14	67	26	4.84	<10	0.40	1123	1	<0.01	4	1560	40	<5	<20	140	0.08	<10	16	<10	7	53
21	G36836	3.7	1.13	60	75	<5	0.73	5	17	55	3346	4.01	20	0.50	258	221	0.03	19	410	146	35	<20	35	0.04	<10	39	<10	9	155
22	G36837	0.4	0.51	30	35	<5	2.96	1	21	67	24	5.12	<10	0.34	956	4	<0.01	5	1620	20	<5	<20	253	0.07	<10	15	<10	8	32
23	G36838	0.4	0.46	30	40	<5	2.76	1	18	70	32	5.35	<10	0.21	843	3	<0.01	5	1940	24	<5	<20	111	0.10	<10	13	<10	9	24
24	G36839	0.5	0.58	25	40	5	2.00	2	19	72	31	7.61	<10	0.44	655	2	<0.01	4	1880	54	<5	<20	204	0.05	<10	14	<10	8	32
25	G36840	0.4	0.46	25	40	5	2.31	1	19	61	19	7.87	<10	0.28	706	9	<0.01	4	1860	46	<5	<20	120	0.02	<10	7	<10	9	22

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36841	0.6	0.37	45	45	10	1.78	2	22	101	17	>10	<10	0.13	535	2	0.01	3	1650	54	5	<20	102	0.01	<10	6	<10	6	17
27	G36842	0.4	0.71	30	40	5	1.24	2	17	98	24	6.51	<10	0.56	492	1	<0.01	4	2220	26	5	<20	71	0.03	<10	21	<10	7	38
28	G36843	0.7	0.61	35	45	<5	1.56	1	15	91	157	7.02	<10	0.52	575	<1	0.01	3	1990	30	<5	<20	101	0.02	<10	17	<10	7	33
29	G36844	4.6	0.22	40	30	<5	0.09	3	14	222	3475	7.33	<10	<0.01	46	13	<0.01	3	570	30	<5	<20	12	<0.01	<10	8	<10	<1	105
30	G36845	3.3	0.19	60	30	<5	0.02	2	13	268	2188	6.33	<10	<0.01	51	12	<0.01	5	250	26	5	<20	6	<0.01	<10	6	<10	<1	96
31	G36846	4.0	0.18	115	30	<5	0.01	3	11	279	2212	5.97	<10	<0.01	46	13	<0.01	5	120	26	15	<20	9	<0.01	<10	7	<10	<1	135
32	G36847	3.5	0.20	40	40	<5	0.03	2	7	273	1710	4.86	<10	<0.01	47	14	<0.01	5	270	32	<5	<20	15	<0.01	<10	7	<10	<1	109
33	G36848	3.7	0.22	45	30	<5	0.08	3	9	268	1663	5.23	<10	<0.01	52	25	<0.01	5	490	50	<5	<20	10	<0.01	<10	9	<10	<1	108
34	G36849	3.2	0.67	40	35	<5	0.12	2	8	258	1744	6.09	<10	0.19	422	23	<0.01	5	770	46	<5	<20	12	<0.01	<10	16	<10	2	159
35	G36850	4.6	0.50	35	35	<5	0.09	4	11	281	2548	6.12	<10	0.13	301	20	0.01	5	640	44	<5	<20	12	<0.01	<10	13	<10	1	214
QC DATA:																													
Repeat:																													
1	G36816	1.1	0.56	45	40	<5	1.31	3	13	100	98	5.78	<10	0.38	628	3	0.01	3	1740	60	20	<20	83	<0.01	<10	11	<10	7	63
10	G36825	0.3	0.94	15	40	<5	2.11	<1	17	44	55	4.90	<10	0.95	820	<1	0.03	5	1860	14	<5	<20	104	0.11	<10	31	<10	8	43
19	G36834	0.3	0.54	15	60	<5	2.29	6	13	74	58	5.04	<10	0.44	801	1	0.01	4	1590	80	<5	<20	233	0.04	<10	15	<10	8	184
Resplit:																													
1	G36816	1.1	0.57	55	45	5	1.83	3	16	97	94	5.55	<10	0.40	708	2	0.01	3	1660	54	25	<20	80	<0.01	<10	11	<10	7	61
Standard:																													
Pb113		11.4	0.22	45	80	<5	1.62	64	3	1	2311	1.06	<10	0.12	1564	73	0.01	1	90	5450	10	<20	85	0.02	<10	8	<10	8	>10000

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
dl/N5505
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5506

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

20-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07054
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36851	1.21	0.035
2	G36852	0.65	0.019
3	G36853	0.79	0.023
4	G36854	0.92	0.027
5	G36855	0.72	0.021
6	G36856	0.79	0.023
7	G36857	0.93	0.027
8	G36858	0.66	0.019
9	G36859	0.68	0.020
10	G36860	<0.03	<0.001
11	G36861	0.97	0.028
12	G36862	1.01	0.029
13	G36863	1.41	0.041
14	G36864	0.77	0.022
15	G36865	0.93	0.027
16	G36866	1.05	0.031
17	G36867	0.87	0.025
18	G36868	1.23	0.036
19	G36869	0.76	0.022
20	G36870	0.29	0.008
21	G36871	0.62	0.018
22	G36872	<0.03	<0.001
23	G36873	0.75	0.022
24	G36874	0.74	0.022
25	G36875	0.83	0.024
26	G36876	1.45	0.042
27	G36877	0.95	0.028
28	G36878	0.93	0.027

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5506 20-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G36879	0.81	0.024
30	G36880	0.66	0.019
31	G36881	0.65	0.019
32	G36882	0.78	0.023
33	G36883	1.13	0.033
34	G36884	0.67	0.020
35	G36885	1.24	0.036

QC DATA:

Repeat:

1	G36851	1.17	0.034
10	G36860	0.03	0.001
19	G36869	0.84	0.024
26	G36876	1.40	0.041
28	G36878	0.90	0.026
32	G36882	0.74	0.022
33	G36883	1.18	0.034
35	G36885	1.24	0.036

Resplits:

1	G36851	1.04	0.030

Standard:

SI25		1.79	0.052
SI25		1.81	0.053

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

22-A

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5506

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07054
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36851	4.1	0.56	35	75	<5	0.07	4	8	264	2759	6.09	<10	0.11	196	20	0.01	4	670	56	<5	<20	9	<0.01	<10	15	<10	2	196
2	G36852	1.9	0.54	20	30	<5	0.11	4	9	207	1722	5.05	<10	0.18	322	18	0.01	3	590	68	<5	<20	13	<0.01	<10	14	<10	2	267
3	G36853	3.1	0.38	60	45	<5	0.12	4	8	241	1455	5.89	<10	0.07	156	23	0.01	4	910	38	<5	<20	13	<0.01	<10	12	<10	3	165
4	G36854	3.0	0.39	65	30	<5	0.12	3	8	234	1621	6.13	<10	0.09	176	19	0.01	4	890	34	5	<20	12	<0.01	<10	12	<10	3	131
5	G36855	3.7	0.45	45	50	<5	0.05	4	8	236	1565	5.41	<10	0.11	198	26	0.01	4	480	40	<5	<20	7	<0.01	<10	16	<10	1	230
6	G36856	2.9	0.38	35	50	<5	0.04	4	9	279	1851	4.65	<10	0.09	155	23	0.01	5	410	54	<5	<20	8	<0.01	<10	14	<10	1	143
7	G36857	3.1	0.85	45	70	<5	0.06	3	11	273	2117	6.20	<10	0.27	452	21	0.01	4	500	42	<5	<20	8	<0.01	<10	27	<10	1	167
8	G36858	2.5	0.80	35	40	<5	0.07	4	8	231	1438	5.05	<10	0.26	456	26	0.01	4	630	42	<5	<20	8	<0.01	<10	21	<10	2	233
9	G36859	2.7	0.88	50	115	<5	0.08	3	12	231	1526	6.63	<10	0.36	450	20	0.01	3	820	32	<5	<20	20	<0.01	<10	31	<10	2	174
10	G36860	0.5	2.68	60	115	<5	0.23	2	40	48	30	7.00	<10	1.88	1148	1	0.01	1	1490	24	<5	<20	25	<0.01	<10	66	<10	6	216
11	G36861	3.8	0.25	170	50	<5	0.07	5	8	270	1745	5.87	<10	<0.01	52	40	0.01	4	530	50	30	<20	8	<0.01	<10	11	<10	2	255
12	G36862	3.2	0.23	80	65	<5	0.04	3	7	248	1778	4.72	<10	<0.01	44	28	0.01	4	410	40	10	<20	9	<0.01	<10	10	<10	1	152
13	G36863	6.9	0.16	95	25	<5	0.03	10	5	255	2163	4.98	<10	<0.01	50	27	0.01	4	300	78	10	<20	6	<0.01	<10	10	<10	<1	523
14	G36864	4.7	0.16	45	35	<5	0.02	2	5	279	1791	3.57	<10	0.02	66	17	0.01	5	180	20	<5	<20	6	<0.01	<10	5	<10	<1	43
15	G36865	3.0	0.65	20	55	<5	0.07	2	5	296	2003	3.96	<10	0.23	226	25	0.01	5	480	20	<5	<20	12	<0.01	<10	8	<10	2	86
16	G36866	4.0	0.68	35	70	<5	0.08	4	9	251	2958	5.21	<10	0.20	200	14	0.01	4	660	32	<5	<20	13	<0.01	<10	9	<10	3	131
17	G36867	3.1	0.88	25	55	<5	0.19	2	6	221	2407	4.36	<10	0.32	383	17	0.01	4	620	22	<5	<20	25	<0.01	<10	12	<10	3	111
18	G36868	3.5	0.82	25	60	<5	0.26	2	5	251	2942	4.74	<10	0.28	364	17	0.01	4	710	24	<5	<20	24	<0.01	<10	12	<10	3	80
19	G36869	2.8	0.51	15	45	<5	0.07	1	5	241	2436	3.36	<10	0.16	159	19	0.01	5	500	18	<5	<20	8	<0.01	<10	9	<10	2	42
20	G36870	2.3	1.15	35	50	<5	1.07	2	21	60	2679	3.53	20	0.55	205	226	0.03	14	660	56	10	<20	62	0.05	<10	41	<10	9	266
21	G36871	2.4	0.25	35	30	<5	0.03	1	5	309	1419	3.19	<10	0.06	89	24	0.01	6	220	14	<5	<20	9	<0.01	<10	6	<10	<1	48
22	G36872	<0.2	1.06	10	275	<5	0.56	<1	8	98	5	2.25	10	0.52	523	3	0.15	11	990	12	<5	<20	98	0.17	<10	44	<10	4	43
23	G36873	2.7	0.42	25	30	<5	0.07	2	9	225	1975	4.30	<10	0.10	126	29	0.01	4	490	26	<5	<20	11	<0.01	<10	8	<10	2	61
24	G36874	2.8	0.65	85	60	<5	0.13	2	7	227	2541	5.31	<10	0.26	299	20	0.01	3	830	30	10	<20	57	<0.01	<10	10	<10	4	64
25	G36875	2.4	0.84	60	60	<5	0.14	1	8	243	2975	4.29	<10	0.44	491	15	0.01	4	640	18	<5	<20	43	<0.01	<10	13	<10	3	86

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36876	3.0	0.75	50	55	<5	0.10	2	13	202	3643	5.57	<10	0.33	326	13	0.01	3	650	22	5	<20	27	<0.01	<10	12	<10	3	72
27	G36877	2.7	0.85	25	45	<5	0.24	1	7	218	2854	4.78	<10	0.38	530	25	0.01	3	560	20	<5	<20	42	<0.01	<10	21	<10	3	69
28	G36878	2.1	0.72	30	45	<5	0.10	1	8	198	2339	5.25	<10	0.39	368	15	0.01	3	680	16	<5	<20	12	<0.01	<10	11	<10	3	74
29	G36879	2.0	0.95	25	65	<5	0.18	1	5	214	2425	4.41	<10	0.43	426	15	0.01	4	700	16	<5	<20	33	<0.01	<10	17	<10	4	80
30	G36880	2.1	0.91	20	75	<5	0.26	1	9	198	2273	3.92	<10	0.44	484	14	0.01	4	760	16	<5	<20	43	<0.01	<10	16	<10	4	70
31	G36881	2.0	0.86	20	70	<5	0.14	1	9	200	1880	3.95	<10	0.34	310	20	<0.01	4	770	16	<5	<20	21	<0.01	<10	13	<10	4	65
32	G36882	2.6	0.83	15	90	<5	0.25	1	6	190	2283	4.14	<10	0.36	431	16	0.01	3	680	18	<5	<20	46	<0.01	<10	19	<10	4	79
33	G36883	3.1	0.80	20	55	<5	0.30	1	9	189	3613	4.33	<10	0.33	428	20	0.01	3	680	16	<5	<20	39	<0.01	<10	14	<10	3	65
34	G36884	2.0	1.05	20	55	<5	0.19	1	7	173	2035	4.22	<10	0.50	478	14	0.01	3	640	16	<5	<20	20	<0.01	<10	13	<10	3	77
35	G36885	3.7	0.65	25	65	<5	0.07	1	8	247	4177	3.95	<10	0.20	230	14	0.01	5	450	22	<5	<20	9	<0.01	<10	9	<10	2	54
QC DATA:																													
Repeat:																													
1	G36851	4.3	0.55	35	150	<5	0.07	4	8	286	2692	6.04	<10	0.11	199	21	0.01	4	650	50	<5	<20	10	<0.01	<10	23	<10	2	188
10	G36860	0.5	2.71	60	130	<5	0.23	2	41	50	31	7.06	<10	1.88	1148	1	0.01	1	1490	24	<5	<20	26	<0.01	<10	69	<10	7	216
19	G36869	2.9	0.60	20	50	<5	0.07	1	5	261	2499	3.45	<10	0.17	165	18	0.01	5	510	18	<5	<20	9	<0.01	<10	13	<10	2	45
Resplit:																													
1	G36851	3.7	0.52	35	65	<5	0.07	3	7	265	2730	5.83	<10	0.09	178	19	0.01	5	670	46	<5	<20	11	<0.01	<10	16	<10	2	195
Standard:																													
Pb113		11.2	0.22	40	75	<5	1.61	51	2	1	2354	1.09	<10	0.10	1558	64	0.02	1	90	5394	<5	<20	86	0.01	<10	7	<10	8	7022

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
df/n5504
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5510

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

28-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07055
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36886	0.76	0.022
2	G36887	0.45	0.013
3	G36888	0.60	0.017
4	G36889	0.63	0.018
5	G36890	0.76	0.022
6	G36891	0.66	0.019
7	G36892	0.84	0.024
8	G36893	0.47	0.014
9	G36894	0.81	0.024
10	G36895	0.91	0.027
11	G36896	<0.03	<0.001
12	G36897	0.73	0.021
13	G36898	0.47	0.014
14	G36899	0.34	0.010
15	G36900	0.44	0.013
16	G36901	0.65	0.019
17	G36902	0.49	0.014
18	G36903	0.27	0.008
19	G36904	0.49	0.014
20	G36905	0.50	0.015
21	G36906	0.49	0.014
22	G36907	0.69	0.020
23	G36908	0.29	0.008
24	G36909	0.40	0.012
25	G36910	1.80	0.052
26	G36911	0.68	0.020

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7 - 5510

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	G36912	0.61	0.018
28	G36913	0.66	0.019
29	G36914	0.06	0.002
30	G36915	0.24	0.007
31	G36916	0.49	0.014
32	G36917	0.34	0.010
33	G36918	0.36	0.010
34	G36919	0.67	0.020
35	G36920	0.50	0.015

QC DATA:

Repeat:

1	G36886	0.72	0.021
10	G36895	0.84	0.024
19	G36904	0.47	0.014

Resplits:

1	G36886	0.69	0.020

Standard:

OXI54		1.84	0.054

AU: 30g FA/AA-Finish

JJ/jl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

27-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5510

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07055
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36886	3.6	0.58	10	35	<5	0.24	1	10	162	2439	3.89	<10	0.28	227	18	0.01	7	490	22	<5	<20	7	<0.01	<10	13	<10	<1	41
2	G36887	2.4	0.80	5	60	<5	0.97	<1	9	125	1724	3.22	<10	0.49	590	22	<0.01	5	630	24	<5	<20	70	0.02	<10	16	<10	3	46
3	G36888	3.2	0.94	5	50	<5	1.02	<1	11	137	2698	3.71	<10	0.59	622	12	<0.01	6	670	30	<5	<20	74	0.01	<10	16	<10	3	56
4	G36889	3.0	1.05	10	75	<5	1.26	<1	9	118	2175	3.66	<10	0.62	752	14	<0.01	5	610	30	<5	<20	89	0.02	<10	18	<10	4	60
5	G36890	3.4	0.90	<5	55	<5	0.63	2	9	154	2913	3.78	<10	0.49	543	19	<0.01	8	420	30	10	<20	51	<0.01	<10	17	<10	2	62
6	G36891	2.9	0.57	5	55	<5	0.44	<1	7	156	2253	2.70	<10	0.27	278	10	<0.01	4	570	24	<5	<20	26	0.01	<10	9	<10	3	36
7	G36892	3.8	0.79	10	45	<5	0.20	<1	8	157	3255	3.80	<10	0.46	286	14	<0.01	6	330	28	<5	<20	14	<0.01	<10	12	<10	2	57
8	G36893	3.0	1.21	10	50	<5	0.34	2	10	109	1668	3.98	<10	0.74	414	15	<0.01	7	720	32	15	<20	18	0.01	<10	16	<10	3	66
9	G36894	3.6	0.59	5	60	<5	0.48	<1	7	185	2570	2.47	<10	0.29	367	24	<0.01	6	390	30	<5	<20	40	<0.01	<10	10	<10	3	37
10	G36895	3.1	0.97	10	75	<5	0.74	2	9	107	2391	4.58	<10	0.63	550	12	0.01	7	580	30	15	<20	78	0.03	<10	30	<10	2	61
11	G36896	<0.2	1.05	<5	255	20	0.57	<1	7	97	8	2.26	<10	0.63	545	3	0.10	8	860	14	10	<20	93	0.11	<10	49	<10	2	41
12	G36897	3.3	0.75	10	45	<5	0.62	1	11	142	2432	3.74	<10	0.44	375	24	<0.01	7	550	32	<5	<20	43	<0.01	<10	12	<10	2	51
13	G36898	2.3	1.09	15	60	<5	0.64	1	9	92	1406	3.77	<10	0.67	466	18	<0.01	6	780	30	5	<20	44	0.01	<10	16	<10	3	70
14	G36899	2.2	0.91	10	65	<5	0.68	1	8	129	1187	3.06	<10	0.58	507	30	<0.01	7	750	34	5	<20	53	0.01	<10	15	<10	4	72
15	G36900	2.3	0.82	<5	80	<5	1.18	1	9	121	1525	3.06	<10	0.50	713	19	0.01	6	690	32	<5	<20	131	0.02	<10	18	<10	4	63
16	G36901	2.9	0.68	10	55	<5	0.83	1	7	120	2106	3.00	<10	0.41	575	18	<0.01	6	530	28	<5	<20	70	<0.01	<10	14	<10	2	54
17	G36902	2.2	0.67	<5	95	<5	1.71	1	7	97	1123	3.32	<10	0.44	771	21	0.01	5	750	28	<5	<20	167	0.01	<10	23	<10	4	58
18	G36903	2.2	0.78	<5	70	<5	1.37	1	9	119	1170	3.55	<10	0.56	674	27	0.02	5	700	32	<5	<20	135	0.02	<10	27	<10	2	77
19	G36904	2.5	0.71	5	55	<5	1.48	<1	11	129	1468	3.65	<10	0.43	608	14	0.02	5	660	38	<5	<20	145	0.02	<10	23	<10	2	64
20	G36905	2.7	1.20	10	65	<5	1.61	1	11	138	1686	3.65	<10	0.88	862	24	<0.01	7	580	38	10	<20	138	0.02	<10	19	<10	3	66
21	G36906	4.1	0.92	15	50	<5	1.34	2	10	101	1457	3.54	<10	0.85	1008	14	<0.01	6	730	52	10	<20	75	0.02	<10	12	<10	4	58
22	G36907	6.1	0.66	10	45	<5	1.09	1	11	159	1740	2.95	<10	0.53	682	19	<0.01	7	530	38	5	<20	64	<0.01	<10	14	<10	3	44
23	G36908	2.9	1.44	<5	65	<5	1.31	<1	12	120	1189	3.79	<10	1.15	864	20	<0.01	6	860	38	15	<20	86	0.02	<10	23	<10	3	73
24	G36909	3.4	0.91	10	45	<5	0.52	<1	10	117	1497	3.56	<10	0.69	463	22	<0.01	5	880	38	<5	<20	21	0.03	<10	15	<10	3	71
25	G36910	4.2	1.02	25	55	<5	1.06	3	23	54	8583	4.04	10	0.66	213	565	0.04	66	90	70	25	<20	57	0.01	<10	44	<10	6	71

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36911	5.0	0.22	15	40	<5	0.42	2	13	174	2138	3.48	<10	0.04	188	53	<0.01	8	410	60	<5	<20	25	<0.01	<10	5	<10	1	44
27	G36912	2.8	0.30	10	30	<5	0.73	<1	13	189	1872	3.07	<10	0.16	370	34	<0.01	7	200	38	<5	<20	31	<0.01	<10	8	<10	<1	18
28	G36913	3.1	1.65	10	60	<5	0.32	<1	17	119	1649	5.04	<10	1.45	575	17	<0.01	18	700	42	<5	<20	20	0.02	<10	34	<10	2	83
29	G36914	1.9	3.55	20	130	<5	2.17	1	31	173	248	5.08	<10	4.30	1253	10	0.01	74	530	68	25	<20	120	0.03	<10	90	<10	5	66
30	G36915	2.7	1.93	20	50	<5	1.17	<1	25	148	1243	4.88	<10	2.10	654	85	<0.01	39	490	70	<5	<20	67	0.03	<10	41	<10	3	58
31	G36916	2.3	3.74	25	90	<5	5.24	2	39	123	427	5.90	<10	4.15	1769	11	<0.01	74	610	70	35	<20	300	0.06	<10	121	<10	7	79
32	G36917	2.6	0.75	10	40	<5	1.92	3	10	170	1350	3.28	<10	0.61	993	27	<0.01	7	450	78	<5	<20	72	0.02	<10	15	<10	3	78
33	G36918	2.2	1.34	15	60	<5	1.79	2	12	101	1157	4.04	<10	1.26	1277	45	<0.01	9	830	64	25	<20	63	0.02	<10	24	<10	4	90
34	G36919	2.4	0.78	5	55	<5	1.51	1	13	147	1839	4.04	<10	0.47	800	38	<0.01	7	460	32	5	<20	53	0.01	<10	16	<10	1	59
35	G36920	2.2	0.65	10	40	<5	0.90	<1	12	149	1713	3.61	<10	0.35	472	58	<0.01	7	660	24	<5	<20	24	0.01	<10	12	<10	3	44
QC DATA:																													
Repeat:																													
1	G36886	3.5	0.59	10	40	<5	0.24	<1	10	163	2418	3.90	<10	0.28	231	17	<0.01	7	490	26	<5	<20	10	<0.01	<10	13	<10	2	42
10	G36895	3.1	0.97	<5	75	<5	0.75	2	9	109	2379	4.61	<10	0.64	553	12	0.01	7	590	30	10	<20	78	0.01	<10	31	<10	3	62
19	G36904	2.6	0.71	<5	55	<5	1.50	<1	11	129	1495	3.70	<10	0.43	620	13	0.01	4	660	40	<5	<20	149	0.02	<10	23	<10	2	66
Resplit:																													
1	G36886	3.2	0.65	20	40	<5	0.24	2	10	157	2337	3.68	<10	0.30	227	20	<0.01	8	590	26	5	<20	7	<0.01	<10	13	<10	2	41
Standard:																													
Pb113		11.4	0.24	45	55	<5	1.74	37	3	6	2213	1.07	<10	0.11	1492	68	0.02	3	80	5520	15	<20	82	<0.01	<10	8	<10	<1	6991

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5510S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5511

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

29-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07056
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34866	0.19	0.006
2	G34867	0.25	0.007
3	G34868	0.33	0.010
4	G34869	0.22	0.006
5	G34870	0.58	0.017
6	G34871	1.14	0.033
7	G34872	0.83	0.024
8	G34873	0.58	0.017
9	G34874	0.42	0.012
10	G34875	0.23	0.007
11	G34876	0.25	0.007
12	G34877	0.17	0.005
13	G34878	0.26	0.008
14	G34879	0.60	0.017
15	G34880	0.31	0.009
16	G34881	0.31	0.009
17	G34882	0.28	0.008
18	G34883	0.46	0.013
19	G34884	0.35	0.010
20	G34885	0.45	0.013
21	G34886	0.19	0.006
22	G34887	0.26	0.008
23	G34888	0.21	0.006
24	G34889	0.20	0.006
25	G34890	1.94	0.057
26	G34891	0.38	0.011

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AW7 - 5511

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	G34892	0.17	0.005
28	G34893	0.34	0.010
29	G34894	1.29	0.038
30	G34895	0.54	0.016
31	G34896	0.09	0.003
32	G34897	<0.03	<0.001
33	G34898	0.11	0.003
34	G34899	0.15	0.004
35	G34900	0.16	0.005
QC DATA:			
Repeat:			
1	G34866	0.19	0.006
6	G34871	1.14	0.033
10	G34875	0.23	0.007
19	G34884	0.37	0.011
29	G34894	1.28	0.037
Resplits:			
1	G34866	0.18	0.005
Standard:			
OXI54		1.85	0.054

AU: 30g FA/AA-Finish

JJ/jl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

27-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5511

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07056
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34866	0.7	0.26	20	60	<5	1.87	<1	9	86	88	1.74	<10	0.51	819	4	0.03	14	550	28	<5	<20	125	0.01	<10	11	<10	3	64
2	G34867	1.4	0.29	35	60	<5	3.06	<1	17	109	390	2.34	<10	0.48	1226	28	0.02	20	530	36	<5	<20	283	0.02	<10	10	<10	5	16
3	G34868	1.3	0.27	45	35	<5	2.41	1	17	88	361	2.81	<10	0.37	844	34	0.04	28	660	80	<5	<20	198	0.02	<10	14	<10	3	26
4	G34869	1.1	0.29	45	60	<5	2.74	<1	36	107	255	3.26	<10	0.44	1159	12	0.04	39	660	28	<5	<20	205	0.02	<10	19	<10	2	14
5	G34870	1.6	0.29	35	65	<5	5.54	2	28	54	465	4.29	<10	1.14	2252	10	0.02	23	1100	24	10	<20	344	0.03	<10	29	<10	5	34
6	G34871	1.4	0.35	45	60	<5	2.75	<1	20	55	413	4.18	<10	0.52	1248	4	0.03	15	1550	26	<5	<20	200	0.03	<10	22	<10	4	16
7	G34872	1.6	0.39	90	55	25	3.68	1	18	47	152	4.77	<10	0.94	1719	4	0.03	10	1540	30	15	<20	232	0.03	<10	23	<10	5	16
8	G34873	1.3	0.39	55	60	<5	4.65	2	18	44	217	3.74	<10	0.88	1752	9	0.02	12	1610	20	25	<20	303	0.02	<10	32	<10	5	15
9	G34874	0.9	0.51	35	60	<5	3.62	<1	17	38	226	2.68	<10	0.39	1331	3	0.03	9	1840	18	10	<20	266	0.02	<10	24	<10	5	11
10	G34875	1.0	0.78	40	75	15	3.92	<1	18	40	166	3.67	<10	0.73	1423	4	0.03	8	1630	24	10	<20	313	0.03	<10	35	<10	5	24
11	G34876	1.0	0.70	65	80	5	3.48	<1	16	51	186	3.55	<10	0.71	1218	4	0.03	9	1750	22	<5	<20	292	0.02	<10	34	<10	5	21
12	G34877	1.0	0.91	35	90	<5	3.34	<1	15	43	180	3.80	<10	1.17	1150	3	0.04	5	1670	28	10	<20	233	0.03	<10	47	<10	4	38
13	G34878	1.6	0.28	45	65	5	4.90	1	14	80	230	4.79	<10	0.85	1724	8	0.03	17	890	30	<5	<20	333	0.03	<10	23	<10	6	21
14	G34879	1.5	0.25	50	45	<5	3.44	1	19	96	442	4.94	<10	0.66	1663	6	0.03	27	660	16	<5	<20	215	0.03	<10	19	<10	2	11
15	G34880	1.5	0.29	55	40	<5	3.76	<1	11	81	139	3.12	<10	0.45	1685	26	0.03	15	720	34	5	<20	261	0.03	<10	11	<10	4	44
16	G34881	1.8	0.33	80	50	5	4.60	<1	13	73	131	4.69	<10	0.24	1540	4	0.04	24	1330	56	<5	<20	316	0.03	<10	13	<10	5	26
17	G34882	0.9	0.28	45	55	15	3.32	<1	7	68	84	2.61	<10	0.81	1276	3	0.05	18	860	18	<5	<20	211	0.02	<10	14	<10	5	30
18	G34883	1.5	0.34	60	60	<5	4.11	2	14	75	341	5.02	<10	0.93	1376	5	0.03	43	870	28	15	<20	279	0.03	<10	18	<10	5	31
19	G34884	1.2	0.35	60	50	20	3.44	<1	11	65	106	3.72	<10	0.88	1248	6	0.04	34	1280	22	5	<20	243	0.03	<10	18	<10	6	28
20	G34885	1.5	0.35	95	55	<5	3.43	1	16	65	259	4.28	<10	0.90	1441	8	0.05	46	1370	20	10	<20	208	0.02	<10	19	<10	3	35
21	G34886	1.0	0.33	60	75	<5	4.43	<1	10	51	117	2.51	<10	0.84	1616	3	0.04	23	1360	36	<5	<20	310	0.03	<10	16	<10	7	89
22	G34887	1.2	0.56	40	70	5	3.89	<1	14	60	206	4.49	<10	1.26	1440	3	0.03	19	1200	24	10	<20	246	0.03	<10	24	<10	4	24
23	G34888	1.7	0.31	60	50	5	3.46	4	9	69	255	3.17	<10	0.71	1049	5	0.04	21	940	170	15	<20	273	0.02	<10	15	<10	6	340
24	G34889	1.4	0.37	90	70	<5	3.80	<1	12	65	146	2.79	<10	0.78	1323	5	0.03	20	1340	24	15	<20	233	0.04	<10	13	<10	6	27
25	G34890	4.1	1.15	60	55	<5	1.12	1	24	59	8609	4.44	10	0.65	204	581	0.04	62	170	78	30	<20	59	0.03	<10	48	<10	6	79

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007- 5511 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34891	1.5	0.38	50	65	<5	4.24	<1	15	45	242	4.04	<10	0.96	1197	6	0.03	38	1510	20	5	<20	225	0.02	<10	23	<10	5	23
27	G34892	0.8	0.32	25	65	<5	3.89	<1	8	54	97	2.06	<10	0.74	1146	2	0.03	12	910	22	<5	<20	240	0.02	<10	18	<10	4	15
28	G34893	1.4	0.34	60	40	<5	2.75	<1	12	55	203	3.27	<10	0.69	845	5	0.02	21	1100	48	<5	<20	233	0.02	<10	12	<10	6	41
29	G34894	3.2	0.34	90	40	10	6.32	3	13	57	174	4.18	<10	1.61	2422	8	0.01	33	750	88	40	<20	382	0.03	<10	12	<10	9	75
30	G34895	1.9	0.47	50	50	<5	6.20	<1	11	66	160	2.31	<10	1.34	2434	10	0.02	19	920	34	20	<20	357	0.03	<10	19	<10	12	52
31	G34896	1.7	0.79	55	45	<5	3.05	<1	12	62	166	2.76	<10	0.55	1088	6	0.03	27	1290	28	10	<20	201	0.04	<10	34	<10	5	16
32	G34897	<0.2	1.10	55	255	30	0.61	<1	9	102	11	2.40	<10	0.62	609	2	0.09	7	970	14	<5	<20	91	0.11	<10	51	<10	3	46
33	G34898	1.9	0.97	65	65	<5	2.10	<1	12	61	199	2.69	<10	0.66	748	14	0.04	25	1060	38	15	<20	167	0.03	<10	40	<10	7	19
34	G34899	3.0	0.84	70	65	<5	3.18	<1	9	72	311	2.64	<10	0.58	1073	13	0.03	26	1230	38	10	<20	227	0.02	<10	33	<10	5	22
35	G34900	1.8	0.45	45	55	<5	2.34	<1	9	97	292	2.44	<10	0.28	722	24	0.05	14	490	52	5	<20	180	0.01	<10	18	<10	4	26
QC DATA:																													
Repeat:																													
1	G34866	0.7	0.29	35	70	<5	1.94	<1	10	92	89	1.80	<10	0.52	846	4	0.03	12	580	34	<5	<20	128	0.01	<10	12	<10	3	66
10	G34875	1.0	0.82	55	70	<5	4.03	1	18	42	166	3.78	<10	0.76	1454	4	0.03	10	1690	24	15	<20	311	0.02	<10	39	<10	4	25
19	G34884	1.2	0.37	55	50	<5	3.39	<1	11	65	102	3.68	<10	0.87	1238	6	0.04	32	1250	20	5	<20	230	0.02	<10	19	<10	5	26
Resplit:																													
1	G34866	0.7	0.29	45	65	<5	2.09	<1	10	99	82	1.80	<10	0.52	850	2	0.03	16	620	38	<5	<20	120	0.02	<10	12	<10	4	68
Standard:																													
Pb113		11.0	0.28	65	65	<5	1.85	38	3	7	2219	1.14	<10	0.13	1567	71	0.02	4	70	5502	15	<20	79	0.01	<10	11	10	<1	6927

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5510S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5512

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

29-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07057
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34901	0.22	0.006
2	G34902	0.20	0.006
3	G34903	0.13	0.004
4	G34904	0.94	0.027
5	G34905	1.51	0.044
6	G34906	0.82	0.024
7	G34907	0.54	0.016
8	G34908	0.74	0.022
9	G34909	0.76	0.022
10	G34910	0.16	0.005
11	G34911	0.33	0.010
12	G34912	0.11	0.003
13	G34913	0.21	0.006
14	G34914	0.54	0.016
15	G34915	1.16	0.034
16	G34916	0.32	0.009
17	G34917	0.61	0.018
18	G34918	0.48	0.014
19	G34919	0.24	0.007
20	G34920	0.13	0.004
21	G34921	0.34	0.010
22	G34922	0.27	0.008
23	G34923	0.24	0.007
24	G34924	0.47	0.014
25	G34925	0.21	0.006
26	G34926	0.15	0.004

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7 - 5512

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	G34927	0.41	0.012
28	G34928	0.92	0.027
29	G34929	0.45	0.013
30	G34930	0.16	0.005
31	G34931	0.14	0.004
32	G34932	0.16	0.005
33	G34933	0.25	0.007
34	G34934	0.29	0.008
35	G34935	<0.03	<0.001

QC DATA:

Repeat:

1	G34901	0.22	0.006
5	G34905	1.58	0.046
10	G34910	0.16	0.005
15	G34915	1.18	0.034
19	G34919	0.25	0.007

Resplits:

1	G34901	0.21	0.006

Standard:

OXI54		1.88	0.055

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
XLS/07

27-Aug-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5512

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07057
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34901	1.6	0.50	25	50	<5	1.93	<1	9	78	480	3.15	<10	0.32	592	16	0.05	14	450	44	5	<20	144	0.02	<10	20	<10	2	24
2	G34902	1.3	0.60	35	65	<5	4.18	<1	7	57	286	2.53	<10	0.41	1258	24	0.03	14	510	30	5	<20	275	0.02	<10	18	<10	5	17
3	G34903	0.9	0.79	30	65	<5	2.95	<1	11	54	240	2.22	<10	0.62	893	5	0.05	20	910	22	5	<20	195	0.02	<10	33	<10	5	22
4	G34904	1.3	0.58	35	50	<5	2.06	1	24	79	419	3.32	<10	0.38	639	17	0.04	18	630	26	10	<20	139	<0.01	<10	25	<10	2	19
5	G34905	1.3	0.63	40	45	<5	2.34	<1	17	86	463	2.65	<10	0.45	711	18	0.06	13	500	34	<5	<20	142	0.02	<10	35	<10	1	19
6	G34906	1.2	0.85	30	45	<5	4.04	<1	13	85	341	3.05	<10	0.75	1335	25	0.05	15	510	28	10	<20	260	0.02	<10	42	<10	4	28
7	G34907	1.8	0.99	45	70	<5	3.97	<1	13	52	234	3.25	<10	0.73	1416	16	0.03	12	1260	38	5	<20	220	0.03	<10	30	<10	4	28
8	G34908	2.4	0.88	50	50	15	4.09	<1	14	57	214	4.26	<10	0.69	1637	5	0.03	12	1440	54	10	<20	210	0.03	<10	33	<10	4	27
9	G34909	3.9	0.85	120	45	5	3.53	2	20	57	179	5.02	<10	0.58	1478	28	0.03	16	1410	198	5	<20	182	0.03	<10	33	<10	4	133
10	G34910	1.3	1.62	40	65	10	2.89	<1	16	45	136	4.44	<10	1.48	1290	7	0.03	11	1770	50	15	<20	167	0.03	<10	74	<10	3	85
11	G34911	1.4	1.13	80	60	15	4.78	<1	18	110	171	3.49	<10	0.96	1567	6	0.04	53	1090	40	10	<20	232	0.03	<10	71	<10	5	37
12	G34912	1.1	0.80	55	45	<5	4.46	<1	21	143	207	3.22	<10	0.68	1292	31	0.05	48	810	22	5	<20	247	0.02	<10	61	<10	2	18
13	G34913	1.2	0.89	70	65	<5	3.95	<1	17	56	304	3.33	<10	0.64	1189	9	0.04	43	1050	26	10	<20	240	0.02	<10	27	<10	5	20
14	G34914	1.2	0.65	70	60	<5	3.30	<1	18	66	222	2.57	<10	0.42	1024	5	0.05	27	1050	28	<5	<20	207	0.02	<10	26	<10	4	15
15	G34915	3.1	0.67	105	40	15	4.03	1	33	45	156	3.61	<10	0.48	1337	8	0.03	36	1200	78	15	<20	230	0.02	<10	23	<10	4	39
16	G34916	1.6	0.97	65	65	<5	2.24	<1	9	50	133	2.43	<10	0.73	780	5	0.06	29	1370	32	15	<20	137	0.02	<10	49	<10	6	31
17	G34917	1.8	0.97	95	55	<5	2.72	<1	30	47	287	4.41	<10	0.64	950	7	0.03	45	1310	58	10	<20	153	0.03	<10	34	<10	4	40
18	G34918	1.4	1.66	50	60	<5	7.16	<1	22	43	350	4.50	<10	1.86	2451	10	0.03	29	1260	40	20	<20	337	0.04	<10	52	<10	6	43
19	G34919	0.9	1.05	40	55	<5	3.19	<1	12	53	250	2.77	<10	0.90	1013	4	0.05	22	1090	28	5	<20	194	0.02	<10	54	<10	5	26
20	G34920	0.9	1.13	40	60	5	3.28	<1	13	43	123	2.27	<10	1.06	1127	4	0.06	23	1380	34	15	<20	187	0.02	<10	50	<10	6	41
21	G34921	1.2	1.45	70	70	5	4.74	<1	11	58	63	3.60	<10	1.35	1640	31	0.04	38	1470	36	20	<20	253	0.03	<10	50	<10	5	47
22	G34922	1.0	0.79	90	60	<5	3.54	<1	8	77	64	2.28	<10	0.58	1125	7	0.05	58	1110	22	15	<20	192	0.02	<10	46	<10	6	20
23	G34923	0.8	0.33	75	40	20	2.45	<1	11	84	28	2.09	<10	0.10	785	9	0.05	29	750	18	<5	<20	127	0.02	<10	11	<10	4	6
24	G34924	1.1	0.46	65	45	20	3.90	<1	10	66	25	2.11	<10	0.31	1367	4	0.04	20	770	32	10	<20	213	0.02	<10	16	<10	6	11
25	G34925	1.3	0.96	65	55	10	4.84	<1	7	53	76	2.74	<10	1.04	1802	11	0.04	22	1010	30	20	<20	264	0.02	<10	31	<10	5	27

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34926	1.1	0.41	50	55	<5	2.51	3	9	79	191	1.67	10	0.33	804	34	0.04	24	570	16	50	<20	167	<0.01	<10	25	<10	2	8
27	G34927	1.4	0.89	25	55	<5	3.48	<1	13	50	164	2.64	<10	0.76	1251	6	0.03	28	990	50	10	<20	176	0.02	<10	28	<10	2	30
28	G34928	1.0	1.20	25	75	<5	4.44	<1	9	43	175	2.65	<10	1.13	1472	5	0.03	30	1190	28	15	<20	223	0.02	<10	25	<10	4	32
29	G34929	1.3	1.47	20	155	10	7.88	<1	5	27	49	3.08	<10	1.84	2595	6	0.02	20	930	34	20	<20	408	0.04	<10	28	<10	6	38
30	G34930	1.5	1.71	10	155	20	>10	1	6	25	67	4.33	<10	1.71	3117	8	0.02	23	850	40	30	<20	538	0.05	<10	29	<10	6	54
31	G34931	1.3	1.28	15	90	20	9.67	<1	10	30	36	3.45	<10	1.26	2889	17	0.02	21	790	38	15	<20	469	0.04	<10	27	<10	6	41
32	G34932	1.4	1.33	10	90	<5	9.81	1	10	28	48	3.58	<10	1.31	2901	12	0.02	25	900	36	15	<20	473	0.04	<10	27	<10	5	45
33	G34933	1.4	1.54	45	65	5	>10	<1	35	29	79	4.17	<10	1.81	3034	30	0.01	43	980	44	20	<20	552	0.04	<10	36	<10	6	50
34	G34934	3.3	1.15	30	60	<5	1.03	3	22	55	2598	3.60	20	0.67	210	179	0.03	11	430	66	15	<20	54	0.04	<10	49	<10	6	278
35	G34935	0.2	1.01	15	230	15	0.59	<1	7	101	7	2.18	<10	0.62	545	4	0.09	6	850	24	10	<20	85	0.09	<10	47	<10	2	42
QC DATA:																													
Repeat:																													
1	G34901	1.6	0.55	40	45	<5	2.02	<1	10	83	494	3.28	<10	0.34	618	16	0.05	14	480	48	<5	<20	149	0.01	<10	23	<10	2	25
10	G34910	1.3	1.68	45	80	10	2.93	<1	17	45	138	4.52	<10	1.53	1312	7	0.03	12	1770	50	20	<20	171	0.03	<10	77	<10	2	86
19	G34919	0.9	1.04	25	60	<5	3.05	<1	12	53	249	2.68	<10	0.91	987	5	0.05	23	1000	26	10	<20	180	0.02	<10	54	<10	3	25
Resplit:																													
1	G34901	1.6	0.51	20	50	<5	2.10	1	9	93	495	3.15	<10	0.33	644	16	0.05	13	440	44	<5	<20	161	0.02	<10	20	<10	1	21
Standard:																													
Pb113		11.2	0.27	70	70	<5	1.72	38	3	6	2278	1.08	<10	0.13	1498	71	0.02	4	80	5438	15	<20	77	<0.01	<10	10	<10	<1	6948

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5510S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5514

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

28-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07058
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G34936	0.31	0.009
2	G34937	0.28	0.008
3	G34938	0.09	0.003
4	G34939	0.08	0.002
5	G34940	<0.03	<0.001
6	G34941	0.05	0.001
7	G34942	0.08	0.002
8	G34943	0.47	0.014
9	G34944	0.13	0.004
10	G34945	0.08	0.002
11	G34946	0.26	0.008
12	G34947	0.20	0.006
13	G34948	0.47	0.014
14	G34949	0.38	0.011
15	G34950	0.98	0.029
16	G34951	0.20	0.006
17	G34952	0.38	0.011
18	G34953	0.20	0.006
19	G34954	0.14	0.004
20	G34955	0.18	0.005
21	G34956	0.12	0.003
22	G34957	0.31	0.009
23	G34958	0.41	0.012
24	G34959	0.30	0.009
25	G34960	0.31	0.009
26	G34961	0.30	0.009

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7 - 5514

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	G34962	0.29	0.008
28	G34963	0.88	0.026
29	G34964	1.21	0.035
30	G34965	0.77	0.022
31	G34966	0.51	0.015
32	G34967	0.77	0.022
33	G34968	0.64	0.019
34	G34969	0.25	0.007
35	G34970	0.40	0.012
QC DATA:			
Repeat:			
1	G34936	0.31	0.009
10	G34945	0.07	0.002
19	G34954	0.14	0.004
29	G34964	1.24	0.036
Resplits:			
1	G34936	0.30	0.009
Standard:			
OXI54		1.86	0.054

AU: 30g FA/AA-Finish

JJ/jl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5514

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07058
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34936	0.3	1.63	50	70	20	9.20	2	19	36	54	3.46	<10	1.92	2867	7	0.02	38	1030	64	20	<20	524	0.04	<10	32	<10	6	65
2	G34937	<0.2	1.72	20	70	20	8.58	1	12	39	73	3.56	<10	2.02	2676	16	0.03	16	760	62	15	<20	516	0.04	<10	49	<10	5	79
3	G34938	0.2	0.99	20	65	<5	3.74	2	6	51	62	1.92	<10	0.97	1350	6	0.06	15	1430	98	20	<20	235	0.02	<10	32	<10	6	69
4	G34939	0.2	1.12	25	75	5	3.54	<1	2	45	22	1.55	<10	1.31	1450	4	0.06	20	1680	72	15	<20	250	0.02	<10	43	<10	8	79
5	G34940	<0.2	1.08	10	280	20	0.60	<1	7	92	5	2.19	<10	0.66	567	4	0.12	7	910	18	10	<20	70	0.12	<10	48	<10	3	44
6	G34941	<0.2	1.15	20	115	<5	5.31	1	3	44	24	1.83	<10	1.41	2161	4	0.06	20	1040	46	15	<20	330	0.03	<10	58	<10	8	56
7	G34942	<0.2	0.95	20	70	<5	3.26	<1	4	49	55	1.51	<10	0.81	1273	6	0.06	15	1270	48	15	<20	191	0.02	<10	36	<10	5	37
8	G34943	0.4	0.88	25	60	15	6.11	<1	14	50	62	2.91	<10	0.77	2203	12	0.04	13	980	74	<5	<20	369	0.03	<10	24	<10	9	33
9	G34944	<0.2	1.53	25	60	10	4.29	<1	18	59	34	3.51	<10	1.71	1546	17	0.06	15	1090	56	10	<20	264	0.03	<10	58	<10	4	48
10	G34945	0.2	1.72	25	65	5	7.40	<1	24	61	43	3.86	<10	2.48	2383	39	0.06	22	1090	78	15	<20	498	0.06	<10	92	<10	6	51
11	G34946	1.1	1.32	55	65	35	7.30	2	14	45	49	4.55	<10	2.36	2977	63	0.02	19	1820	98	30	<20	396	0.04	<10	42	<10	5	61
12	G34947	0.2	0.69	30	40	<5	3.29	<1	30	54	51	2.86	<10	0.73	914	9	0.05	17	1180	38	10	<20	162	0.02	<10	22	<10	2	24
13	G34948	0.3	0.38	25	40	<5	2.20	<1	23	57	136	2.65	<10	0.53	747	7	0.06	19	660	26	20	<20	124	<0.01	<10	18	<10	1	19
14	G34949	0.5	0.52	55	40	<5	2.84	3	12	59	88	3.38	<10	0.79	990	17	0.05	23	870	72	45	<20	147	<0.01	<10	21	<10	1	62
15	G34950	3.7	1.09	60	55	<5	0.72	2	17	54	3277	3.87	20	0.53	275	202	0.03	13	330	126	20	<20	35	0.03	<10	43	<10	6	151
16	G34951	0.2	0.67	30	50	20	6.43	<1	8	47	50	3.29	<10	2.66	2075	8	0.03	10	690	44	25	<20	210	0.03	<10	21	<10	6	38
17	G34952	0.7	0.60	70	40	20	2.26	<1	15	62	33	4.03	<10	0.72	815	10	0.05	20	1120	68	<5	<20	107	0.02	<10	22	<10	2	26
18	G34953	0.4	1.27	10	45	10	4.53	<1	8	45	148	4.17	<10	1.43	1671	8	0.04	17	1180	64	10	<20	234	0.03	<10	40	<10	4	73
19	G34954	0.6	0.82	20	45	25	3.92	<1	8	54	81	3.79	<10	1.14	1695	10	0.04	15	1060	48	<5	<20	197	0.03	<10	23	<10	5	42
20	G34955	0.3	1.21	30	50	25	5.53	<1	17	42	66	3.61	<10	1.75	1878	22	0.03	21	1340	40	15	<20	299	0.03	<10	35	<10	6	45
21	G34956	0.4	0.89	50	25	<5	3.16	3	13	54	47	1.89	20	0.93	864	34	0.05	27	960	28	65	<20	171	<0.01	<10	41	<10	<1	26
22	G34957	0.4	0.95	55	30	<5	3.51	2	11	32	175	2.01	<10	0.99	975	15	0.03	29	1500	16	40	<20	173	<0.01	<10	27	<10	1	28
23	G34958	0.4	1.15	30	50	<5	5.21	<1	18	29	268	2.54	<10	1.26	1546	15	0.03	22	1550	24	15	<20	316	0.02	<10	30	<10	5	31
24	G34959	0.2	2.06	15	50	10	>10	1	7	36	38	3.76	<10	2.81	4271	36	0.01	13	490	42	20	<20	579	0.05	<10	60	<10	6	54
25	G34960	0.4	1.66	35	65	20	5.66	<1	9	29	53	3.47	<10	1.76	2067	34	0.02	23	1120	58	15	<20	319	0.03	<10	37	<10	6	50

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34961	0.3	1.31	25	60	20	3.78	1	12	38	48	2.74	<10	1.24	1407	10	0.02	21	1670	38	10	<20	201	0.02	<10	26	<10	8	46
27	G34962	0.8	0.46	35	60	25	4.18	<1	10	55	16	1.86	<10	0.22	1502	4	0.01	12	700	54	<5	<20	232	0.02	<10	8	<10	5	10
28	G34963	0.8	0.67	30	50	20	3.14	1	16	42	23	3.94	<10	0.44	1248	7	0.01	23	1110	68	<5	<20	183	0.02	<10	12	<10	4	27
29	G34964	1.0	0.95	35	55	35	5.53	1	10	47	97	3.83	<10	1.12	2575	5	0.01	16	760	44	25	<20	290	0.03	<10	17	<10	6	56
30	G34965	0.6	0.65	40	75	45	1.75	<1	14	42	23	4.01	<10	0.29	651	7	0.03	27	1510	48	<5	<20	145	0.03	<10	12	<10	8	21
31	G34966	0.5	0.58	50	40	25	2.53	<1	24	42	13	3.05	<10	0.19	877	5	0.02	24	1500	30	<5	<20	176	0.02	<10	12	<10	5	10
32	G34967	0.7	0.53	30	50	40	2.89	1	14	62	52	4.48	<10	0.39	1183	7	0.03	44	720	30	<5	<20	202	0.03	<10	20	<10	2	23
33	G34968	0.7	0.53	35	50	20	2.10	<1	13	83	41	3.65	<10	0.40	773	7	0.05	33	660	26	10	<20	175	0.02	<10	24	<10	2	26
34	G34969	0.4	0.37	50	50	45	1.60	<1	15	102	18	2.84	<10	0.19	546	17	0.06	21	580	22	<5	<20	157	0.02	<10	18	<10	2	14
35	G34970	0.7	0.68	65	45	35	2.38	<1	19	83	24	4.49	<10	0.60	913	9	0.05	42	820	36	<5	<20	194	0.03	<10	46	<10	4	31
QC DATA:																													
Repeat:																													
1	G34936	0.3	1.69	55	85	5	9.36	2	19	37	54	3.54	<10	1.95	2914	8	0.02	40	1100	66	25	<20	545	0.04	<10	34	<10	6	67
10	G34945	0.2	1.72	20	55	30	7.13	<1	24	59	40	3.91	<10	2.48	2330	36	0.05	21	920	74	15	<20	457	0.05	<10	92	<10	4	52
19	G34954	0.5	0.82	15	55	15	3.71	<1	8	52	81	3.67	<10	1.14	1649	10	0.04	15	1130	46	5	<20	194	0.03	<10	22	<10	5	40
Resplit:																													
1	G34936	0.4	1.70	55	75	10	8.91	<1	15	33	48	3.76	<10	2.12	2875	8	0.02	36	1060	78	20	<20	501	0.04	<10	34	<10	7	74
Standard:																													
Pb113		10.9	0.25	45	65	<5	1.60	45	2	2	2302	1.08	<10	0.10	1561	59	0.01	<1	70	5584	<5	<20	70	<0.01	<10	9	<10	1	7072

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/1208S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5516

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

29-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07059
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36921	0.44	0.013
2	G36922	0.67	0.020
3	G36923	0.66	0.019
4	G36924	0.63	0.018
5	G36925	0.62	0.018
6	G36926	0.63	0.018
7	G36927	0.58	0.017
8	G36928	0.86	0.025
9	G36929	0.58	0.017
10	G36930	0.24	0.007
11	G36931	0.19	0.006
12	G36932	0.33	0.010
13	G36933	0.35	0.010
14	G36934	0.59	0.017
15	G36935	0.42	0.012
16	G36936	<0.03	<0.001
17	G36937	0.33	0.010
18	G36938	0.38	0.011
19	G36939	0.33	0.010
20	G36940	0.27	0.008
21	G36941	0.31	0.009
22	G36942	0.24	0.007
23	G36943	0.29	0.008
24	G36944	0.51	0.015
25	G36945	0.54	0.016
26	G36946	0.59	0.017
27	G36947	0.39	0.011

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 29-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G36948	0.28	0.008
29	G36949	0.30	0.009
30	G36950	0.55	0.016
31	G36951	0.99	0.029
32	G36952	0.33	0.010
33	G36953	0.28	0.008
34	G36954	0.56	0.016
35	G36955	0.36	0.010

QC DATA:

Repeat:

1	G36921	0.44	0.013
10	G36930	0.23	0.007
19	G36939	0.35	0.010
31	G36951	1.05	0.031

Resplits:

1	G36921	0.46	0.013

Standard:

Oxi54		1.84	0.054

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

30-/ 17

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5516

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07059
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36921	1.5	0.82	5	50	<5	0.94	1	11	172	1411	3.82	<10	0.50	562	60	0.01	7	450	22	<5	<20	38	0.01	<10	17	<10	2	59
2	G36922	2.0	0.67	95	45	<5	0.29	2	12	151	1693	3.73	<10	0.32	239	59	0.01	6	540	22	<5	<20	17	0.01	<10	12	<10	2	50
3	G36923	2.1	0.98	50	50	<5	0.16	1	10	185	1669	3.98	<10	0.68	366	27	0.01	7	460	30	5	<20	11	0.01	<10	20	<10	<1	76
4	G36924	2.2	0.95	15	40	<5	0.16	1	11	178	1789	4.14	<10	0.68	401	34	0.01	6	370	32	<5	<20	11	0.01	<10	20	<10	<1	71
5	G36925	2.1	0.85	20	40	<5	0.17	1	10	145	1716	4.17	<10	0.59	366	33	0.01	6	350	30	<5	<20	9	0.01	<10	19	<10	<1	64
6	G36926	3.0	0.91	25	45	<5	0.16	<1	12	147	1940	4.37	<10	0.62	325	27	0.01	6	600	38	<5	<20	15	0.01	<10	18	<10	2	75
7	G36927	2.3	1.30	20	55	<5	0.25	<1	10	110	1666	4.47	<10	0.94	478	34	<0.01	6	940	36	10	<20	15	0.02	<10	20	<10	3	106
8	G36928	2.0	1.26	25	55	<5	1.03	1	10	147	1108	5.36	<10	0.70	819	30	0.01	6	830	52	<5	<20	60	0.02	<10	19	<10	7	108
9	G36929	1.5	1.57	30	60	<5	1.00	2	8	128	1145	4.99	<10	0.93	910	33	<0.01	6	550	84	10	<20	65	0.02	<10	23	<10	5	128
10	G36930	0.9	0.93	10	45	<5	0.91	<1	11	119	891	3.53	<10	0.47	530	50	0.01	5	890	30	<5	<20	47	0.01	<10	13	<10	5	61
11	G36931	0.8	0.98	15	55	<5	0.60	1	9	112	550	3.38	<10	0.57	387	72	0.01	8	1140	24	15	<20	26	0.01	<10	16	<10	4	70
12	G36932	1.6	0.99	5	55	<5	0.75	1	10	102	1000	3.42	<10	0.63	484	131	0.01	5	1000	26	<5	<20	36	0.01	<10	15	<10	5	70
13	G36933	0.8	1.35	15	65	<5	0.61	<1	8	108	738	3.78	<10	0.94	604	52	0.01	4	980	30	<5	<20	31	0.02	<10	21	<10	3	95
14	G36934	1.2	1.39	10	65	<5	0.84	1	10	116	1149	3.86	<10	1.04	782	75	0.01	4	890	32	5	<20	46	0.02	<10	22	<10	3	82
15	G36935	1.1	0.93	10	50	<5	0.52	<1	10	106	1055	3.40	<10	0.63	438	69	0.01	6	870	28	<5	<20	33	0.03	<10	14	<10	4	71
16	G36936	<0.2	1.00	20	240	25	0.56	<1	7	102	5	2.15	<10	0.59	533	1	0.11	4	900	18	<5	<20	78	0.11	<10	46	<10	4	44
17	G36937	1.1	1.19	10	60	<5	1.07	<1	8	109	654	3.58	<10	0.89	757	61	0.01	6	930	28	10	<20	62	0.02	<10	20	<10	5	76
18	G36938	1.0	1.11	15	55	<5	1.41	<1	10	169	708	3.43	<10	0.74	810	46	0.01	6	780	28	<5	<20	85	0.02	<10	20	<10	4	68
19	G36939	0.8	1.19	15	55	<5	1.02	<1	11	97	727	3.73	<10	0.90	716	65	0.01	4	960	32	<5	<20	61	0.02	<10	22	<10	3	81
20	G36940	1.0	1.13	<5	60	<5	0.37	3	10	122	696	3.88	<10	0.78	410	49	<0.01	6	970	30	5	<20	18	0.02	<10	21	<10	2	103
21	G36941	1.3	1.00	20	40	<5	0.32	<1	12	135	909	3.86	<10	0.66	342	44	0.01	6	1030	38	<5	<20	16	0.01	<10	16	<10	2	83
22	G36942	0.8	0.97	15	55	<5	0.30	3	8	108	532	3.12	<10	0.61	321	32	0.01	6	1170	26	15	<20	17	<0.01	<10	17	<10	3	108
23	G36943	1.4	0.96	10	40	<5	0.33	2	11	119	806	4.60	<10	0.60	343	44	0.01	6	1080	38	<5	<20	18	0.02	<10	18	<10	3	87
24	G36944	2.6	0.77	15	30	<5	0.31	2	11	190	2098	3.37	<10	0.46	317	41	0.01	6	580	30	<5	<20	7	0.01	<10	14	<10	<1	88
25	G36945	2.4	0.51	<5	40	<5	0.22	<1	10	157	2096	3.30	<10	0.32	182	32	0.01	5	520	26	<5	<20	15	<0.01	<10	13	<10	<1	58

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36946	1.8	0.54	<5	40	<5	0.68	1	10	177	1527	3.62	<10	0.36	436	39	0.01	6	360	38	<5	<20	41	0.01	<10	15	<10	<1	51
27	G36947	1.2	1.21	10	70	<5	1.69	1	8	123	981	3.47	<10	0.84	876	136	0.02	6	760	30	10	<20	106	0.02	<10	23	<10	4	76
28	G36948	1.1	1.60	10	90	<5	1.86	1	8	137	841	3.72	<10	1.19	1155	28	0.01	5	950	48	10	<20	109	0.03	<10	27	<10	6	117
29	G36949	3.2	1.12	35	50	<5	0.99	2	20	54	2620	3.33	20	0.60	197	199	0.03	12	460	52	<5	<20	53	0.04	<10	45	<10	7	262
30	G36950	1.7	2.01	15	90	<5	0.78	1	9	111	1460	4.60	<10	1.53	1110	52	0.01	6	1030	50	15	<20	40	0.02	<10	30	<10	4	143
31	G36951	2.8	1.40	5	65	<5	0.44	2	9	171	3156	4.22	<10	0.87	733	103	0.01	7	540	58	10	<20	23	<0.01	<10	25	<10	<1	128
32	G36952	1.0	1.08	20	60	<5	0.59	1	9	156	938	3.67	<10	0.70	728	41	0.01	5	660	68	<5	<20	29	0.02	<10	20	<10	1	109
33	G36953	1.1	1.17	15	65	<5	0.72	2	8	132	943	3.51	<10	0.84	799	40	0.01	8	650	50	15	<20	45	0.01	<10	23	<10	2	115
34	G36954	1.4	1.11	15	60	<5	0.79	<1	7	154	1343	3.44	<10	0.80	855	150	0.01	5	630	46	5	<20	45	0.02	<10	23	<10	2	114
35	G36955	1.2	1.16	10	65	<5	1.03	3	10	119	1027	3.33	<10	0.85	1002	52	0.01	6	670	74	10	<20	71	0.02	<10	22	<10	2	155
QC DATA:																													
Repeat:																													
1	G36921	1.5	0.81	15	45	<5	0.95	<1	12	166	1427	3.84	<10	0.50	565	57	0.01	6	450	22	<5	<20	37	0.02	<10	16	<10	2	59
10	G36930	1.1	0.91	10	45	<5	0.91	<1	11	115	883	3.55	<10	0.46	531	45	<0.01	6	930	32	<5	<20	45	0.02	<10	13	<10	5	63
19	G36939	0.8	1.16	<5	55	<5	1.02	<1	11	92	732	3.72	<10	0.90	714	67	0.01	5	960	32	<5	<20	60	0.02	<10	21	<10	3	81
Resplit:																													
1	G36921	1.5	0.82	10	45	<5	0.89	1	11	135	1413	3.80	<10	0.51	550	51	0.01	7	490	22	10	<20	37	0.02	<10	16	<10	2	62
Standard:																													
Pb113		11.4	0.25	40	55	<5	1.63	35	2	5	2269	1.02	<10	0.10	1594	67	0.02	2	90	5556	20	<20	80	0.01	<10	7	<10	<1	6905

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Julia Jealouse
B.C. Certified Assayer

JJ/jl
dl/5516a
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5517

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Aug-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07060
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36956	0.33	0.010
2	G36957	0.46	0.013
3	G36958	0.43	0.013
4	G36959	0.59	0.017
5	G36960	0.40	0.012
6	G36961	0.32	0.009
7	G36962	0.40	0.012
8	G36963	0.40	0.012
9	G36964	0.32	0.009
10	G36965	0.44	0.013
11	G36966	0.45	0.013
12	G36967	0.29	0.008
13	G36968	0.35	0.010
14	G36969	0.38	0.011
15	G36970	0.94	0.027
16	G36971	0.36	0.010
17	G36972	0.43	0.013
18	G36973	0.62	0.018
19	G36974	0.45	0.013
20	G36975	0.41	0.012
21	G36976	0.52	0.015
22	G36977	0.75	0.022
23	G36978	0.65	0.019
24	G36979	0.40	0.012
25	G36980	0.19	0.006
26	G36981	0.31	0.009
27	G36982	0.52	0.015

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 30-Aug-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G36983	<0.03	<0.001
29	G36984	0.49	0.014
30	G36985	0.65	0.019
31	G36986	0.30	0.009
32	G36987	0.69	0.020
33	G36988	0.67	0.020
34	G36989	0.45	0.013
35	G36990	0.47	0.014
QC DATA:			
Repeat:			
1	G36956	0.31	0.009
10	G36965	0.44	0.013
19	G36974	0.45	0.013
Resplits:			
1	G36956	0.34	0.010
Standard:			
OXI54		1.83	0.053

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5517

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07060
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36956	1.0	0.95	25	60	<5	1.81	2	12	154	767	3.80	<10	0.50	951	69	0.02	5	870	104	<5	<20	128	0.02	<10	24	<10	3	229
2	G36957	1.0	1.11	40	180	<5	2.04	1	9	115	1094	4.20	<10	0.63	1100	43	0.02	5	890	62	10	<20	147	0.02	<10	32	<10	3	192
3	G36958	1.1	0.93	30	85	<5	1.91	2	11	160	975	3.34	<10	0.52	998	86	0.01	5	820	70	<5	<20	126	0.02	<10	21	<10	4	159
4	G36959	1.8	0.99	30	60	<5	1.37	6	12	169	1480	3.60	<10	0.56	1008	61	0.01	6	750	430	10	<20	78	0.02	<10	20	<10	3	379
5	G36960	1.7	0.90	20	65	<5	0.87	2	11	151	1499	3.42	<10	0.48	699	56	0.01	5	690	54	5	<20	54	0.01	<10	18	<10	2	166
6	G36961	1.2	1.15	35	95	<5	1.53	1	10	185	871	3.69	<10	0.62	878	60	0.01	8	860	50	15	<20	90	0.02	<10	22	<10	3	155
7	G36962	1.0	1.17	25	120	<5	1.76	<1	15	23	4087	3.68	<10	0.99	728	7	0.17	14	1270	36	10	<20	170	0.14	<10	168	<10	8	47
8	G36963	1.4	0.88	35	60	<5	1.06	<1	12	152	1259	3.43	<10	0.49	655	73	0.01	7	710	44	5	<20	77	0.01	<10	19	<10	3	79
9	G36964	1.6	1.00	30	80	<5	1.37	<1	9	153	1319	3.28	<10	0.54	787	46	0.01	6	800	44	10	<20	77	0.01	<10	18	<10	3	81
10	G36965	1.9	1.05	30	80	<5	1.34	2	11	145	1651	3.44	<10	0.56	730	107	0.01	6	820	44	10	<20	74	0.01	<10	20	<10	3	94
11	G36966	1.9	1.11	30	85	<5	1.65	2	10	159	1384	3.44	<10	0.61	965	231	0.01	6	870	68	5	<20	95	0.02	<10	21	<10	4	121
12	G36967	1.8	1.34	35	95	<5	0.92	2	7	165	1488	3.72	<10	0.82	815	94	0.01	7	910	76	15	<20	58	0.02	<10	25	<10	4	145
13	G36968	2.2	1.12	35	110	<5	2.17	1	9	135	1401	3.48	<10	0.67	1165	196	0.01	6	830	48	5	<20	134	0.02	<10	22	<10	5	149
14	G36969	2.0	0.93	25	90	<5	2.57	1	10	130	1506	3.33	<10	0.56	1102	100	0.02	4	970	42	5	<20	190	0.02	<10	29	<10	5	132
15	G36970	2.3	0.97	25	65	<5	1.41	2	11	159	1679	4.22	<10	0.59	793	52	0.03	6	970	38	5	<20	108	0.02	<10	41	<10	3	199
16	G36971	1.2	0.87	15	160	<5	2.47	2	10	122	990	3.17	<10	0.46	1020	62	0.02	4	1210	36	10	<20	187	0.02	<10	28	<10	5	139
17	G36972	1.7	0.86	25	155	<5	2.33	2	10	122	1164	3.19	<10	0.50	988	58	0.02	7	1110	36	15	<20	170	0.01	<10	26	<10	5	122
18	G36973	2.5	0.88	25	95	<5	2.34	3	13	160	1950	4.12	<10	0.49	991	45	0.02	7	1010	34	5	<20	163	0.02	<10	34	<10	3	232
19	G36974	1.6	0.84	25	250	<5	2.56	2	10	163	1149	3.86	<10	0.42	1114	59	0.02	6	1180	44	5	<20	174	0.02	<10	36	<10	4	154
20	G36975	1.5	0.91	20	200	<5	2.22	3	11	153	1531	4.13	<10	0.54	977	47	0.03	6	1040	42	<5	<20	158	0.02	<10	49	<10	3	197
21	G36976	2.1	0.94	35	60	<5	2.11	<1	18	191	1714	4.11	<10	0.58	988	74	0.01	8	860	58	5	<20	139	0.02	<10	35	<10	3	121
22	G36977	2.5	0.95	30	55	<5	1.83	2	11	143	2223	3.39	<10	0.59	893	416	0.02	4	970	46	<5	<20	108	0.02	<10	33	<10	5	126
23	G36978	1.8	1.10	20	145	<5	1.82	2	11	118	1453	4.32	<10	0.72	1074	102	0.03	6	1090	84	10	<20	147	0.02	<10	53	<10	4	167
24	G36979	1.5	0.96	25	195	<5	2.07	2	10	117	1360	3.40	<10	0.60	940	71	0.03	5	1180	38	5	<20	149	0.03	<10	41	<10	5	150
25	G36980	1.0	0.95	25	125	<5	2.22	<1	12	99	575	3.44	<10	0.54	943	29	0.02	4	1310	42	<5	<20	150	0.04	<10	33	<10	5	122

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G36981	1.5	0.90	30	135	<5	2.41	3	11	110	1166	3.46	<10	0.54	944	48	0.03	5	1210	70	5	<20	149	0.02	<10	35	<10	4	196
27	G36982	1.4	1.03	25	100	<5	2.13	<1	11	141	1447	4.31	<10	0.68	853	87	0.03	7	1150	34	5	<20	129	0.02	<10	45	<10	4	74
28	G36983	<0.2	1.06	30	265	10	0.69	<1	8	134	8	2.48	<10	0.55	580	4	0.13	6	1010	30	<5	<20	96	0.15	<10	48	<10	5	49
29	G36984	1.6	1.03	35	125	<5	2.21	<1	12	115	1284	4.31	<10	0.70	878	54	0.04	4	1210	40	5	<20	146	0.03	<10	61	<10	4	94
30	G36985	1.6	0.95	35	90	<5	2.27	<1	14	131	1484	4.38	<10	0.61	860	96	0.03	6	1150	40	<5	<20	142	0.03	<10	49	<10	4	90
31	G36986	1.4	0.84	35	110	<5	2.45	<1	11	160	1006	3.28	<10	0.40	875	54	0.02	6	1250	36	<5	<20	140	0.02	<10	25	<10	5	75
32	G36987	2.0	1.01	35	70	<5	2.08	10	10	184	1246	3.54	<10	0.54	796	140	0.02	6	1320	606	<5	<20	134	0.02	<10	25	<10	5	504
33	G36988	2.9	0.67	35	40	<5	1.46	<1	9	161	2323	2.58	<10	0.40	530	83	0.02	5	810	48	<5	<20	100	0.01	<10	26	<10	5	58
34	G36989	1.7	1.06	30	50	<5	1.41	<1	11	126	1357	4.22	<10	0.74	666	107	0.04	6	1250	32	10	<20	115	0.02	<10	56	<10	3	67
35	G36990	1.8	1.01	30	50	<5	1.68	<1	13	134	1528	4.19	<10	0.75	771	64	0.05	7	1070	34	<5	<20	151	0.03	<10	68	<10	5	62
QC DATA:																													
Repeat:																													
1	G36956	0.9	0.89	30	60	<5	1.78	3	12	146	750	3.70	<10	0.49	931	65	0.02	6	850	102	10	<20	124	0.02	<10	23	<10	3	224
10	G36965	1.8	1.04	30	80	<5	1.37	1	11	141	1675	3.47	<10	0.56	734	107	0.01	7	840	42	5	<20	78	0.01	<10	19	<10	3	92
19	G36974	1.6	0.82	20	240	<5	2.61	3	10	157	1158	3.93	<10	0.43	1128	64	0.02	8	1210	44	10	<20	176	0.02	<10	36	<10	3	158
Resplit:																													
1	G36956	1.0	0.91	25	55	<5	1.85	3	13	146	773	3.61	<10	0.44	1010	76	0.02	5	760	110	<5	<20	128	0.02	<10	21	<10	2	223
Standard:																													
Pb113		9.3	0.28	90	70	<5	1.81	43	3	7	2253	1.17	<10	0.16	1508	108	0.02	11	120	6054	85	<20	145	<0.01	420	15	20	<1	7057

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5507dS
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5518

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07061
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G36991	0.49	0.014
2	G36992	0.89	0.026
3	G36993	0.63	0.018
4	G36994	1.04	0.030
5	G36995	0.74	0.022
6	G36996	0.41	0.012
7	G36997	0.55	0.016
8	G36998	0.52	0.015
9	G36999	0.39	0.011
10	G37000	0.46	0.013
11	G37001	1.87	0.055
12	G37002	0.43	0.013
13	G37003	0.34	0.010
14	G37004	0.52	0.015
15	G37005	0.49	0.014
16	G37006	0.48	0.014
17	G37007	0.39	0.011
18	G37008	0.35	0.010
19	G37009	0.27	0.008
20	G37010	0.34	0.010
21	G37011	0.30	0.009
22	G37012	0.53	0.015
23	G37013	0.54	0.016
24	G37014	0.36	0.010
25	G37015	0.41	0.012
26	G37016	0.30	0.009
27	G37017	0.58	0.017
28	G37018	0.79	0.023

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc.

4-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G37019	0.79	0.023
30	G37020	0.48	0.014
31	G37021	0.32	0.009
32	G37022	<0.03	<0.001
33	G37023	0.46	0.013
34	G37024	0.33	0.010
35	G37025	0.33	0.010

QC DATA:

Repeat:

1	G36991	0.50	0.015
10	G37000	0.50	0.015
19	G37009	0.26	0.008

Resplits:

1	G36991	0.52	0.015

Standard:

OXI54		1.87	0.055

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

4-S 07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5518

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07061
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G36991	2.1	0.96	<5	65	<5	1.66	58	10	113	1366	3.89	<10	0.73	686	57	0.04	7	930	2698	10	<20	124	0.03	<10	55	<10	1	2833
2	G36992	2.4	0.76	25	80	<5	1.81	<1	10	119	2114	2.74	<10	0.48	654	70	0.02	6	860	28	<5	<20	122	0.02	<10	23	<10	4	43
3	G36993	2.2	0.96	10	80	<5	1.97	<1	10	107	1901	3.09	<10	0.71	717	116	0.03	6	980	26	10	<20	143	0.03	<10	32	<10	5	45
4	G36994	2.6	0.71	15	55	<5	1.24	<1	9	136	2928	2.55	<10	0.52	458	213	0.02	5	550	26	<5	<20	81	0.02	<10	27	<10	4	33
5	G36995	1.6	0.89	<5	55	<5	1.82	1	11	107	1854	3.44	<10	0.63	708	101	0.02	7	850	58	5	<20	123	0.02	<10	39	<10	4	52
6	G36996	1.2	1.06	10	105	<5	1.76	<1	12	87	1252	3.92	<10	0.78	757	61	0.04	4	1160	28	<5	<20	131	0.05	<10	58	<10	4	62
7	G36997	2.1	1.05	10	55	<5	1.79	<1	13	101	1826	4.06	<10	0.81	843	44	0.03	7	1080	26	<5	<20	122	0.04	<10	48	<10	4	53
8	G36998	2.0	0.95	15	60	<5	2.03	<1	13	92	1889	3.56	<10	0.68	850	43	0.03	6	1040	28	10	<20	140	0.03	<10	42	<10	5	46
9	G36999	2.3	0.89	20	40	<5	2.06	<1	14	116	1342	3.67	<10	0.68	1208	22	0.02	5	900	34	<5	<20	140	0.04	<10	36	<10	3	74
10	G37000	2.1	1.07	20	65	<5	1.81	1	14	130	1444	4.31	<10	0.86	980	109	0.04	7	1020	30	10	<20	121	0.05	<10	52	<10	4	56
11	G37001	3.9	1.11	35	55	<5	0.99	3	22	56	8747	4.05	10	0.60	195	571	0.04	60	210	66	30	<20	54	0.02	<10	43	<10	6	69
12	G37002	2.0	0.97	10	65	<5	2.30	1	13	88	1220	3.60	<10	0.74	1194	31	0.04	6	1140	24	<5	<20	161	0.04	<10	46	<10	4	53
13	G37003	2.1	0.96	10	40	<5	2.47	1	14	119	1261	3.94	<10	0.75	1364	52	0.03	6	1040	26	<5	<20	175	0.05	<10	44	<10	3	44
14	G37004	1.6	0.99	10	65	<5	1.71	1	14	106	1414	3.71	<10	0.83	814	56	0.05	6	1020	28	10	<20	125	0.06	<10	62	<10	4	47
15	G37005	2.0	1.06	25	65	<5	2.12	<1	14	115	1580	3.64	<10	0.86	972	67	0.04	6	1100	26	10	<20	162	0.05	<10	49	<10	5	49
16	G37006	1.6	0.90	30	55	<5	1.97	<1	11	135	1264	3.13	<10	0.69	913	40	0.03	7	1020	24	10	<20	126	0.03	<10	38	<10	4	46
17	G37007	1.5	1.00	20	100	<5	2.07	<1	11	89	1099	3.67	<10	0.79	831	60	0.04	5	1200	24	<5	<20	157	0.05	<10	58	<10	4	54
18	G37008	1.1	0.95	15	135	<5	2.49	<1	13	87	1042	3.91	<10	0.69	919	32	0.06	5	1190	28	<5	<20	213	0.06	<10	79	<10	4	61
19	G37009	0.8	1.00	20	140	<5	2.35	1	12	75	714	3.99	<10	0.73	985	24	0.05	6	1300	26	10	<20	183	0.07	<10	71	<10	4	66
20	G37010	1.2	0.93	10	95	<5	2.36	1	11	98	908	3.51	<10	0.66	1072	33	0.04	6	1130	24	10	<20	202	0.05	<10	55	<10	4	56
21	G37011	2.6	0.93	20	60	<5	2.31	<1	12	104	1078	3.15	<10	0.68	1291	25	0.03	4	1170	24	<5	<20	187	0.06	<10	37	<10	3	55
22	G37012	3.0	0.97	20	65	<5	2.10	2	14	80	1698	3.69	<10	0.77	1021	88	0.04	7	1100	28	20	<20	162	0.04	<10	48	<10	4	55
23	G37013	2.7	1.14	30	80	<5	2.06	1	14	90	1465	3.76	<10	0.86	1047	195	0.04	5	1240	48	5	<20	165	0.07	<10	53	<10	8	83
24	G37014	1.8	1.07	10	100	<5	2.95	1	15	48	1219	3.82	<10	0.75	1293	39	0.04	6	1420	28	10	<20	231	0.07	<10	59	<10	5	80
25	G37015	1.2	1.07	15	95	<5	2.86	1	13	80	1180	4.06	<10	0.77	999	32	0.05	5	1330	30	5	<20	228	0.07	<10	66	<10	5	67

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37016	1.3	1.15	15	90	<5	2.43	<1	13	86	1012	3.78	<10	0.86	871	37	0.05	5	1230	30	10	<20	205	0.07	<10	59	<10	5	60
27	G37017	4.2	1.08	25	85	<5	2.28	<1	12	92	1696	2.68	<10	0.84	986	85	0.02	6	1280	32	10	<20	150	0.05	<10	39	<10	5	65
28	G37018	20.3	0.82	35	80	<5	3.85	4	10	111	3217	2.34	<10	0.57	1463	83	0.02	5	990	120	10	<20	260	0.04	<10	22	<10	5	214
29	G37019	10.3	0.91	35	70	<5	2.64	1	10	100	2249	3.01	<10	0.67	1527	44	0.01	5	1280	102	5	<20	148	0.05	<10	24	<10	6	116
30	G37020	6.3	0.93	30	75	<5	2.46	1	13	95	1488	3.02	<10	0.61	1252	42	0.01	5	1320	74	10	<20	140	0.05	<10	24	<10	5	113
31	G37021	2.1	1.14	25	225	<5	3.17	<1	12	72	895	3.37	<10	0.74	1257	105	0.03	5	1450	34	10	<20	235	0.07	<10	44	<10	7	79
32	G37022	<0.2	1.04	15	245	25	0.61	<1	7	96	6	2.16	<10	0.58	531	4	0.11	6	960	26	10	<20	97	0.13	<10	46	<10	3	44
33	G37023	2.1	1.11	20	80	<5	2.33	1	13	99	1187	3.17	<10	0.81	1048	63	0.03	7	1290	30	20	<20	173	0.05	<10	40	<10	4	65
34	G37024	1.6	1.12	30	90	<5	2.53	<1	13	75	942	3.40	<10	0.78	1098	76	0.03	4	1290	32	10	<20	228	0.05	<10	37	<10	5	71
35	G37025	1.5	1.05	20	90	<5	2.94	<1	12	82	847	3.07	<10	0.74	1212	46	0.02	5	1110	28	5	<20	254	0.05	<10	32	<10	4	64
QC DATA:																													
Repeat:																													
1	G36991	2.1	0.95	5	60	<5	1.66	58	10	115	1360	3.86	<10	0.72	683	55	0.04	5	960	2700	5	<20	126	0.03	<10	54	<10	2	2826
19	G37009	0.8	1.01	15	130	<5	2.41	<1	13	77	723	4.08	<10	0.74	1005	23	0.05	4	1340	26	<5	<20	190	0.08	<10	71	<10	4	68
Resplit:																													
1	G36991	2.1	0.95	5	65	<5	1.71	58	10	120	1408	3.94	<10	0.73	693	57	0.04	8	910	2670	10	<20	129	0.03	<10	56	<10	3	2873
Standard:																													
PB113		11.9	0.27	60	60	<5	1.68	35	3	6	2290	1.06	<10	0.10	1411	78	0.02	3	70	5464	20	<20	84	0.01	<10	8	10	<1	6940

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl/sa
df/5518
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5526

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07062
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37026	0.81	0.024
2	G37027	0.43	0.013
3	G37028	0.38	0.011
4	G37029	0.51	0.015
5	G37030	0.41	0.012
6	G37031	0.51	0.015
7	G37032	0.36	0.010
8	G37033	0.59	0.017
9	G37034	0.46	0.013
10	G37035	0.33	0.010
11	G37036	<0.03	<0.001
12	G37037	0.62	0.018
13	G37038	0.67	0.020
14	G37039	0.88	0.026
15	G37040	0.45	0.013
16	G37041	0.37	0.011
17	G37042	0.70	0.020
18	G37043	0.36	0.010
19	G37044	0.59	0.017
20	G37045	0.36	0.010
21	G37046	0.26	0.008
22	G37047	0.55	0.016
23	G37048	0.25	0.007
24	G37049	0.44	0.013
25	G37050	0.25	0.007

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7- 5526 4-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	G37051	0.41	0.012
27	G37052	0.54	0.016
28	G37053	0.31	0.009
29	G37054	0.37	0.011
30	G37055	0.40	0.012
31	G37056	0.68	0.020
32	G37057	0.31	0.009
33	G37058	0.18	0.005
34	G37059	0.46	0.013
35	G37060	0.27	0.008

QC DATA:

Repeat:

1	G37026	0.73	0.021
10	G37035	0.30	0.009
19	G37044	0.59	0.017

Resplits:

1	G37026	0.76	0.022

Standard:

OXI54		1.88	0.055
OXI54		1.87	0.055

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/bp
XLS/07

4-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5526

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07062
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37026	2.2	1.16	15	75	<5	1.81	<1	15	104	1768	4.08	<10	0.80	792	165	0.04	6	1230	34	5	<20	127	0.06	<10	61	<10	5	71
2	G37027	1.5	1.22	15	90	<5	2.43	1	14	63	1324	4.00	<10	0.88	1074	63	0.04	6	1340	34	5	<20	199	0.06	<10	59	<10	3	74
3	G37028	1.4	1.09	15	75	<5	2.18	<1	15	76	1061	3.52	<10	0.73	972	73	0.03	4	1390	32	<5	<20	164	0.05	<10	43	<10	5	73
4	G37029	2.0	1.11	30	100	<5	1.72	<1	13	80	1468	2.97	<10	0.72	934	61	0.02	5	1340	36	5	<20	123	0.05	<10	34	<10	5	87
5	G37030	3.1	1.04	25	70	<5	0.81	<1	15	93	1816	3.17	<10	0.67	788	79	0.02	6	1360	88	10	<20	51	0.03	<10	32	<10	5	88
6	G37031	3.0	0.93	30	85	<5	0.71	1	13	97	1415	3.06	<10	0.59	700	80	0.01	6	1310	248	5	<20	42	0.03	<10	31	<10	5	108
7	G37032	6.8	0.35	20	55	<5	1.60	43	12	114	2003	5.07	<10	0.06	754	75	<0.01	6	780	1232	<5	<20	138	0.03	<10	12	<10	4	2338
8	G37033	5.2	0.88	30	50	<5	1.52	2	16	112	3288	3.58	<10	0.60	911	120	0.02	7	1110	66	15	<20	168	0.02	<10	35	<10	6	130
9	G37034	2.5	1.26	30	75	<5	1.54	<1	14	79	1382	3.23	<10	0.98	1181	59	0.03	6	1490	36	10	<20	110	0.05	<10	48	<10	6	126
10	G37035	2.5	1.09	35	65	<5	2.80	1	17	85	1256	3.37	<10	0.78	1528	102	0.03	6	1360	64	10	<20	224	0.06	<10	43	<10	6	188
11	G37036	<0.2	1.10	35	250	25	0.66	<1	8	101	10	2.23	<10	0.60	556	4	0.12	6	910	20	5	<20	94	0.14	<10	47	<10	3	48
12	G37037	2.9	1.19	20	85	<5	2.39	<1	16	66	1580	4.00	<10	0.83	1307	74	0.04	5	1510	32	5	<20	178	0.05	<10	63	<10	5	98
13	G37038	2.8	1.26	30	85	<5	1.79	<1	15	72	2023	3.90	<10	0.92	921	128	0.03	6	1310	32	10	<20	200	0.06	<10	59	<10	4	99
14	G37039	4.7	1.11	25	45	<5	2.16	1	13	99	3974	3.29	<10	0.82	928	429	0.03	5	1210	36	10	<20	170	0.05	<10	43	<10	5	70
15	G37040	1.8	1.42	35	90	<5	2.50	2	16	52	1380	4.56	<10	1.09	1295	71	0.03	7	1540	38	10	<20	176	0.06	<10	68	<10	7	99
16	G37041	1.9	1.30	25	95	<5	2.06	1	14	67	1072	3.28	<10	0.94	1131	50	0.03	5	1560	36	10	<20	160	0.06	<10	46	<10	6	100
17	G37042	1.5	1.04	35	80	<5	2.60	<1	12	76	913	3.06	<10	0.71	1067	92	0.02	5	1340	30	5	<20	188	0.05	<10	37	<10	5	72
18	G37043	1.4	1.13	35	125	<5	2.41	<1	11	78	904	2.91	<10	0.76	838	137	0.03	5	1450	30	<5	<20	171	0.06	<10	43	<10	6	64
19	G37044	3.7	1.25	25	100	<5	2.75	2	14	76	1988	3.83	<10	0.84	1228	175	0.02	5	1280	60	5	<20	201	0.06	<10	43	<10	6	87
20	G37045	2.0	1.12	25	90	<5	3.10	<1	17	67	732	3.60	<10	0.70	1403	18	0.02	6	1530	36	5	<20	258	0.06	<10	39	<10	5	81
21	G37046	1.1	1.21	15	120	<5	2.14	1	16	64	736	3.93	<10	0.81	1005	35	0.04	6	1590	34	5	<20	134	0.07	<10	55	<10	5	92
22	G37047	1.4	1.20	10	130	<5	2.34	3	18	50	1221	5.25	<10	0.84	1078	40	0.04	5	1430	30	<5	<20	146	0.08	<10	63	<10	3	130
23	G37048	0.6	1.02	10	205	<5	2.95	<1	11	70	612	3.81	<10	0.73	1171	169	0.05	5	1400	28	5	<20	223	0.08	<10	69	<10	5	85
24	G37049	1.5	0.89	15	55	<5	2.09	1	16	110	1450	3.33	<10	0.68	864	78	0.04	6	1010	32	10	<20	135	0.06	<10	45	<10	5	69
25	G37050	0.7	1.18	20	85	<5	1.85	<1	14	87	829	3.53	<10	0.93	790	86	0.04	5	1370	46	5	<20	121	0.08	<10	60	<10	6	69

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007- 5526 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37051	1.3	1.16	20	75	<5	1.44	<1	13	121	1138	3.44	<10	0.86	738	50	0.03	6	1250	32	5	<20	85	0.06	<10	48	<10	3	61
27	G37052	1.4	0.97	20	80	<5	2.13	<1	12	96	1222	3.01	<10	0.68	848	108	0.03	5	1270	30	10	<20	111	0.06	<10	45	<10	5	57
28	G37053	3.0	1.20	45	45	<5	1.01	2	22	58	2585	3.60	20	0.62	198	203	0.03	10	550	62	5	<20	53	0.05	<10	47	<10	6	285
29	G37054	2.2	1.13	25	80	<5	2.89	2	11	87	1271	2.87	<10	0.81	1038	121	0.02	7	1290	36	20	<20	134	0.04	<10	36	<10	7	80
30	G37055	3.3	1.23	20	85	<5	2.81	<1	13	77	1143	3.12	<10	0.87	1245	78	0.02	5	1370	38	5	<20	163	0.05	<10	35	<10	5	88
31	G37056	3.2	1.14	15	60	<5	3.46	2	16	62	830	3.77	<10	0.84	1504	31	0.03	6	1430	34	15	<20	202	0.06	<10	41	<10	5	97
32	G37057	1.4	1.28	25	55	<5	3.01	<1	25	66	1189	4.08	<10	1.00	1149	62	0.02	7	1470	38	10	<20	169	0.07	<10	45	<10	7	84
33	G37058	0.8	1.31	30	85	<5	2.27	<1	13	71	851	3.39	<10	1.01	898	65	0.04	4	1530	42	15	<20	131	0.08	<10	57	<10	7	89
34	G37059	1.5	1.30	35	65	<5	2.52	<1	18	88	1172	4.22	<10	1.08	978	86	0.04	7	1340	48	10	<20	148	0.09	<10	58	<10	7	86
35	G37060	0.6	1.20	25	55	<5	1.99	<1	13	73	681	3.32	<10	1.01	771	148	0.04	4	1490	34	<5	<20	88	0.09	<10	57	<10	6	57
QC DATA:																													
Repeat:																													
1	G37026	2.2	1.16	20	80	<5	1.80	<1	14	111	1753	4.05	<10	0.80	788	164	0.04	7	1220	34	10	<20	128	0.06	<10	61	<10	5	70
10	G37035	2.6	1.14	30	65	<5	2.88	3	18	87	1299	3.47	<10	0.83	1577	114	0.03	9	1380	62	20	<20	237	0.04	<10	46	<10	6	193
19	G37044	3.6	1.19	20	95	<5	2.73	1	14	76	1963	3.79	<10	0.82	1219	166	0.02	4	1250	58	5	<20	197	0.06	<10	41	<10	6	87
Resplit:																													
1	G37026	2.4	1.12	15	70	<5	1.86	<1	16	98	1881	3.93	<10	0.82	786	167	0.04	6	1280	36	10	<20	131	0.05	<10	57	<10	6	70
Standard:																													
Pb113		11.7	0.27	65	55	<5	1.69	36	3	6	2315	1.07	<10	0.11	1418	82	0.02	2	70	5390	20	<20	72	0.02	<10	9	10	<1	6999

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5518S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5527

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07063
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	G34971	1.33	0.039		
2	G34972	0.40	0.012		
3	G34973	0.45	0.013		
4	G34974	0.40	0.012		
5	G34975	0.84	0.024		
6	G34976	1.05	0.031		
7	G34977	0.81	0.024		
8	G34978	0.22	0.006		
9	G34979	0.41	0.012		
10	G34980	0.68	0.020		
11	G34981	0.31	0.009		
12	G34982	0.82	0.024		
13	G34983	0.29	0.008		
14	G34984	0.32	0.009		
15	G34985	0.30	0.009		
16	G34986	1.55	0.045		
17	G34987	0.53	0.015		
18	G34988	2.54	0.074		
19	G34989	0.32	0.009	32.6	0.951
20	G34990	<0.03	<0.001		
21	G34991	0.40	0.012		
22	G34992	0.34	0.010		
23	G34993	0.15	0.004		
24	G34994	0.19	0.006		
25	G34995	0.19	0.006		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5527 4-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
26	G34996	0.23	0.007		
27	G34997	0.41	0.012		
28	G34998	0.24	0.007		
29	G34999	0.23	0.007		
30	G35000	0.26	0.008		
31	G35001	0.22	0.006		
32	G35002	0.26	0.008		
33	G35003	0.31	0.009		
34	G35004	0.22	0.006		
35	G35005	0.38	0.011		
QC DATA:					
Repeat:					
1	G34971	1.30	0.038		
10	G34980	0.62	0.018		
18	G34988	2.44	0.071		
19	G34989	0.34	0.010		
Standard:					
OXi54		1.89	0.055		
OXi54		1.87	0.055		
Pb113				22.7	0.662

AU: 30g FA/AA-Finish

JJ/bp
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

4-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5527

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07063
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G34971	0.7	0.93	35	65	15	2.79	<1	9	59	99	3.17	<10	0.81	1015	4	0.05	30	1360	36	10	<20	217	0.03	<10	44	<10	4	45
2	G34972	0.4	0.71	40	50	5	3.19	<1	7	65	19	3.00	<10	0.45	1282	4	0.05	16	850	26	10	<20	207	0.03	<10	30	<10	3	23
3	G34973	0.6	0.32	45	45	20	1.99	<1	9	64	11	2.38	<10	0.05	781	6	0.05	20	890	28	<5	<20	127	0.02	<10	16	<10	3	11
4	G34974	1.9	0.28	35	45	5	2.08	4	5	62	33	1.91	<10	0.06	1065	7	0.05	16	670	554	15	<20	123	0.02	<10	19	<10	3	455
5	G34975	1.1	0.34	60	50	20	3.62	1	13	55	39	4.73	<10	0.04	2006	4	0.03	29	1430	34	<5	<20	214	0.04	<10	13	<10	4	58
6	G34976	1.2	0.36	75	40	25	6.16	<1	14	56	52	4.42	<10	0.25	4269	<1	0.01	30	1410	32	<5	<20	346	0.07	<10	11	<10	4	66
7	G34977	1.4	0.31	40	35	10	2.16	<1	5	54	43	2.24	<10	0.04	1204	2	0.04	30	930	26	10	<20	113	0.02	<10	11	<10	1	25
8	G34978	0.7	0.40	45	50	10	1.76	<1	8	82	8	2.83	<10	0.10	961	2	0.04	24	740	46	<5	<20	102	0.02	<10	13	<10	3	18
9	G34979	1.0	1.26	35	45	<5	2.78	<1	15	68	755	4.67	<10	1.22	858	73	0.01	5	1570	40	10	<20	78	0.02	<10	29	<10	1	50
10	G34980	1.8	1.19	20	45	<5	1.92	<1	18	77	908	4.57	<10	1.26	860	78	0.01	5	1620	60	15	<20	70	0.03	<10	29	<10	2	56
11	G34981	0.6	1.19	20	50	<5	3.31	<1	16	74	614	3.93	<10	0.96	808	45	0.02	5	1650	42	10	<20	178	0.02	<10	31	<10	3	60
12	G34982	2.1	1.08	45	50	<5	1.59	<1	15	77	572	4.23	<10	0.82	603	110	0.01	6	1630	50	10	<20	98	0.02	<10	27	<10	3	44
13	G34983	0.5	1.69	35	35	<5	0.98	<1	17	55	399	4.64	<10	1.56	667	54	0.01	7	1730	52	15	<20	45	0.02	<10	38	<10	2	72
14	G34984	0.4	1.33	25	40	<5	1.53	<1	19	77	458	4.56	<10	1.30	874	32	0.01	7	1670	52	15	<20	46	0.03	<10	34	<10	2	53
15	G34985	0.8	1.45	30	45	<5	1.87	2	17	73	717	4.71	<10	1.48	827	55	0.01	8	2000	40	25	<20	46	0.02	<10	36	<10	3	67
16	G34986	3.2	0.84	130	45	<5	1.44	3	20	82	570	5.06	<10	0.81	719	86	0.01	9	1630	46	65	<20	46	0.02	<10	25	<10	2	68
17	G34987	4.3	1.11	65	40	<5	1.12	2	18	74	474	5.08	<10	1.12	645	136	0.01	8	1830	44	35	<20	33	0.02	<10	31	<10	2	65
18	G34988	5.8	0.90	110	45	<5	0.87	2	16	65	338	4.57	<10	0.74	401	67	0.01	6	1650	56	45	<20	34	0.02	<10	23	<10	3	70
19	G34989	>30	1.90	145	45	<5	1.76	9	18	72	699	4.60	<10	1.82	908	109	0.01	8	1630	1480	125	<20	53	0.03	<10	45	<10	2	574
20	G34990	<0.2	1.11	25	250	15	0.68	<1	8	96	6	2.24	<10	0.61	572	2	0.11	6	890	18	<5	<20	88	0.14	<10	49	<10	3	40
21	G34991	4.4	1.16	85	45	<5	1.46	2	17	82	425	5.17	<10	1.25	959	102	0.01	7	1650	102	45	<20	41	0.03	<10	29	<10	2	112
22	G34992	1.5	1.79	50	55	<5	2.14	2	14	74	394	3.98	<10	1.57	942	57	0.01	7	1760	94	25	<20	75	0.03	<10	41	<10	5	209
23	G34993	1.0	1.61	20	50	<5	2.36	2	19	76	457	5.61	<10	1.41	956	73	0.02	8	1700	80	20	<20	77	0.03	<10	38	<10	3	63
24	G34994	1.6	1.51	35	45	<5	1.43	1	18	75	657	5.09	<10	1.39	899	130	0.01	6	1670	76	10	<20	63	0.03	<10	39	<10	3	90
25	G34995	0.8	1.44	35	45	<5	2.07	<1	17	69	465	4.36	<10	1.35	1069	53	0.01	6	1740	64	20	<20	60	0.03	<10	37	<10	5	132

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G34996	0.9	1.50	35	40	<5	2.15	3	18	74	581	4.57	<10	1.45	1120	81	0.01	9	1700	76	30	<20	66	0.03	<10	41	<10	5	129
27	G34997	1.0	1.13	10	115	<5	1.74	<1	14	22	3928	3.58	<10	1.08	727	2	0.16	13	1340	36	5	<20	107	0.13	<10	174	<10	5	46
28	G34998	0.7	1.69	30	55	<5	2.16	1	17	70	510	4.66	<10	1.53	854	44	0.02	8	1710	58	15	<20	78	0.03	<10	46	<10	4	73
29	G34999	0.6	1.78	30	40	<5	2.57	1	17	73	510	4.59	<10	1.53	904	63	0.02	6	1720	54	10	<20	89	0.03	<10	48	<10	4	66
30	G35000	1.3	1.97	30	45	<5	3.21	<1	18	58	644	4.64	<10	1.66	1191	110	0.02	7	1690	56	15	<20	108	0.03	<10	47	<10	4	67
31	G35001	0.9	2.26	40	60	<5	1.02	<1	17	65	481	4.63	<10	1.92	699	73	0.01	8	1860	56	30	<20	59	0.02	<10	51	<10	3	82
32	G35002	2.8	1.32	60	40	<5	1.28	2	17	72	504	4.29	<10	1.36	1098	73	0.01	7	1690	96	30	<20	84	0.03	<10	36	<10	3	162
33	G35003	1.3	1.67	45	40	<5	1.72	<1	17	61	724	4.68	<10	1.77	1297	85	0.01	6	1780	86	20	<20	58	0.03	<10	41	<10	4	145
34	G35004	0.8	2.03	35	60	<5	1.25	<1	16	63	418	4.69	<10	1.68	853	272	0.01	5	1790	66	10	<20	68	0.03	<10	45	<10	3	85
35	G35005	1.4	1.63	45	40	<5	1.05	1	17	80	815	4.66	<10	1.40	905	95	0.01	8	1670	98	20	<20	42	0.03	<10	38	<10	3	92

QC DATA:

Repeat:

1	G34971	0.8	0.93	40	60	10	2.86	<1	10	59	102	3.22	<10	0.83	1035	4	0.05	30	1400	36	10	<20	224	0.03	<10	44	<10	4	45
10	G34980	1.6	1.26	20	50	<5	1.92	1	17	75	911	4.58	<10	1.27	860	78	0.01	6	1600	60	10	<20	61	0.02	<10	31	<10	2	56
19	G34989	>30	1.89	155	40	<5	1.76	8	18	71	718	4.63	<10	1.85	918	93	0.01	7	1600	1494	115	<20	55	0.03	<10	45	<10	3	569

Resplit:

1	G34971	0.8	0.83	35	60	15	2.81	1	11	60	91	3.28	<10	0.71	1043	4	0.05	32	1360	40	10	<20	214	0.03	<10	38	<10	4	39

Standard:

PB113		11.8	0.27	45	50	<5	1.75	42	1	4	2139	1.09	10	0.21	1459	67	0.02	13	90	5526	25	<20	80	<0.01	<10	19	<10	<1	6935

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/bp
df/5518
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10011 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5528

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07064
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35006	0.35	0.010
2	G35007	0.28	0.008
3	G35008	0.48	0.014
4	G35009	0.35	0.010
5	G35010	0.48	0.014
6	G35011	0.53	0.015
7	G35012	0.41	0.012
8	G35013	0.23	0.007
9	G35014	0.22	0.006
10	G35015	0.37	0.011
11	G35016	0.33	0.010
12	G35017	0.61	0.018
13	G35018	0.56	0.016
14	G35019	0.65	0.019
15	G35020	0.42	0.012
16	G35021	0.56	0.016
17	G35022	1.03	0.030
18	G35023	1.73	0.050
19	G35024	1.12	0.033
20	G35025	1.06	0.031
21	G35026	0.75	0.022
22	G35027	0.56	0.016
23	G35028	0.70	0.020
24	G35029	0.74	0.022
25	G35030	0.30	0.009

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5528 4-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	G35031	0.63	0.018
27	G35032	0.55	0.016
28	G35033	0.71	0.021
29	G35034	0.47	0.014
30	G35035	0.41	0.012
31	G35036	0.71	0.021
32	G35037	1.18	0.034
33	G35038	1.64	0.048
34	G35039	0.98	0.029
35	G35040	<0.03	<0.001

QC DATA:

Repeat:

1	G35006	0.34	0.010
10	G35015	0.32	0.009
18	G35023	1.78	0.052
19	G35024	1.10	0.032
33	G35038	1.77	0.052

Resplits:

1	G35006	0.40	0.012

Standard:

OXI54		1.88	0.055
OXI54		1.85	0.054

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/bp
XLS/07

4-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5528

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07064
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35006	1.2	1.93	15	55	<5	0.97	1	20	50	881	4.92	<10	1.62	740	178	0.01	7	1560	62	20	<20	39	0.02	<10	43	<10	2	72
2	G35007	0.8	1.89	15	45	<5	1.13	1	15	52	600	4.46	<10	1.54	825	160	0.01	5	1510	60	10	<20	38	0.03	<10	39	<10	2	76
3	G35008	1.3	1.70	15	40	<5	0.92	2	20	74	1050	5.09	<10	1.42	826	268	<0.01	6	1560	66	10	<20	29	0.03	<10	39	<10	1	93
4	G35009	1.0	1.94	25	45	<5	0.68	2	14	70	912	4.73	<10	1.65	714	65	<0.01	7	1530	54	15	<20	20	0.02	<10	37	<10	2	99
5	G35010	1.4	0.93	25	35	<5	0.76	2	15	89	937	4.04	<10	0.77	603	165	<0.01	6	1440	74	10	<20	23	0.02	<10	22	<10	1	79
6	G35011	1.2	1.62	15	40	<5	1.71	2	18	69	991	4.35	<10	1.52	1199	135	0.01	6	1510	84	10	<20	62	0.03	<10	37	<10	3	106
7	G35012	1.0	1.72	15	40	<5	1.29	2	17	49	741	4.24	<10	1.50	921	86	0.01	6	1570	60	10	<20	55	0.02	<10	38	<10	3	107
8	G35013	0.7	1.92	15	55	<5	1.52	1	17	50	548	4.29	<10	1.72	1131	41	0.02	6	1620	52	15	<20	58	0.03	<10	43	<10	4	115
9	G35014	0.9	1.46	30	40	<5	1.16	<1	17	53	592	4.25	<10	1.39	933	38	0.01	5	1610	60	<5	<20	44	0.03	<10	37	<10	3	81
10	G35015	0.7	1.77	5	45	<5	1.56	2	15	48	599	4.51	<10	1.70	1060	76	0.01	6	1490	54	15	<20	43	0.03	<10	41	<10	3	68
11	G35016	0.8	1.95	15	45	<5	1.67	2	17	60	665	4.98	<10	1.82	1079	201	0.01	9	1450	52	30	<20	54	0.02	<10	40	<10	2	75
12	G35017	7.2	1.33	15	45	<5	0.65	3	18	75	1199	5.61	<10	1.13	586	115	<0.01	8	1420	272	15	<20	22	0.03	<10	32	<10	<1	85
13	G35018	8.3	1.06	70	35	<5	0.95	4	17	108	1331	4.50	<10	0.99	879	288	0.01	5	1280	76	40	<20	24	0.02	<10	30	<10	1	131
14	G35019	9.2	1.20	55	40	<5	0.83	3	16	76	1286	4.86	<10	1.11	793	88	<0.01	6	1430	158	30	<20	29	0.03	<10	28	<10	2	155
15	G35020	3.4	1.34	10	35	<5	0.75	1	16	70	1033	4.57	<10	1.25	742	55	<0.01	6	1420	50	5	<20	18	0.02	<10	33	<10	<1	91
16	G35021	8.1	1.41	45	40	<5	0.92	5	16	77	1271	4.13	<10	1.29	889	88	<0.01	6	1520	70	25	<20	31	0.02	<10	33	<10	2	134
17	G35022	3.0	0.92	10	45	<5	2.09	1	12	81	1961	3.29	<10	0.56	940	17	0.01	6	1410	66	<5	<20	54	0.02	<10	22	<10	3	65
18	G35023	10.8	0.62	90	50	<5	1.09	4	14	121	1934	4.04	<10	0.29	615	33	0.01	7	1020	140	35	<20	39	0.02	<10	17	<10	2	103
19	G35024	6.4	0.38	105	30	<5	1.16	5	18	160	3927	4.27	<10	0.13	664	52	0.01	8	450	232	40	<20	31	0.01	<10	12	<10	<1	268
20	G35025	4.1	0.54	35	40	<5	1.87	2	12	100	3337	3.33	<10	0.26	736	17	0.02	6	970	54	10	<20	64	<0.01	<10	17	<10	1	61
21	G35026	2.4	0.56	25	45	<5	3.71	4	11	94	1650	2.99	<10	0.32	1233	36	0.01	5	1180	72	5	<20	152	0.02	<10	16	<10	3	202
22	G35027	1.6	0.62	10	55	<5	3.67	2	11	81	1152	3.13	<10	0.46	868	22	0.02	6	1190	26	10	<20	183	0.02	<10	23	<10	2	61
23	G35028	2.3	0.65	10	55	<5	3.40	1	10	99	1643	3.11	<10	0.47	853	19	0.02	6	1100	48	5	<20	191	0.02	<10	22	<10	3	62
24	G35029	2.4	0.46	<5	35	<5	3.26	6	10	81	1569	2.72	<10	0.39	870	15	0.01	4	1200	48	<5	<20	97	0.02	<10	16	<10	3	253
25	G35030	3.0	1.11	35	50	<5	0.93	3	20	53	2620	3.45	20	0.59	185	189	0.03	9	460	60	10	<20	45	0.04	<10	44	<10	5	264

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35031	2.2	0.40	15	30	<5	2.39	3	13	106	1763	3.83	<10	0.30	804	19	<0.01	6	1060	30	<5	<20	54	0.02	<10	13	<10	<1	95
27	G35032	3.2	0.36	15	40	<5	2.71	2	13	88	1889	3.05	<10	0.21	648	17	0.01	5	1140	52	<5	<20	95	0.02	<10	12	<10	2	63
28	G35033	3.3	0.40	<5	30	<5	1.88	2	10	95	2016	2.84	<10	0.35	589	20	<0.01	5	1110	24	<5	<20	77	0.01	<10	11	<10	2	49
29	G35034	7.5	0.36	15	45	<5	1.78	4	16	95	2018	4.09	<10	0.19	542	23	<0.01	5	1080	128	<5	<20	46	0.02	<10	11	<10	1	164
30	G35035	2.5	0.30	<5	35	<5	2.26	2	17	94	1641	5.52	<10	0.31	888	27	<0.01	6	1210	34	<5	<20	51	0.03	<10	9	<10	<1	20
31	G35036	2.6	0.63	10	45	<5	2.71	2	17	99	1429	3.48	<10	0.53	983	24	<0.01	6	1090	56	10	<20	58	0.02	<10	18	<10	2	69
32	G35037	2.4	0.49	<5	40	<5	1.77	2	11	96	1453	3.83	<10	0.28	533	21	0.02	6	1090	26	<5	<20	36	0.02	<10	25	<10	1	25
33	G35038	3.3	0.53	<5	35	<5	1.12	2	10	113	2571	3.66	<10	0.31	419	21	0.03	8	890	22	10	<20	51	<0.01	<10	29	<10	2	36
34	G35039	2.2	0.40	<5	35	<5	1.34	3	11	68	1395	3.62	<10	0.17	381	20	<0.01	6	1210	86	<5	<20	37	0.03	<10	12	<10	1	121
35	G35040	<0.2	1.01	<5	240	20	0.56	<1	6	88	6	2.03	<10	0.59	506	1	0.12	4	780	14	<5	<20	85	0.12	<10	43	<10	3	42
QC DATA:																													
Repeat:																													
1	G35006	1.1	1.87	20	45	<5	0.96	<1	20	47	862	4.81	<10	1.59	726	168	0.01	6	1560	58	<5	<20	38	0.03	<10	41	<10	<1	70
10	G35015	0.7	1.79	10	40	<5	1.57	2	15	48	610	4.54	<10	1.72	1070	81	0.01	7	1470	52	20	<20	42	0.03	<10	42	<10	2	68
19	G35024	6.4	0.37	90	25	<5	1.13	6	17	153	3827	4.16	<10	0.13	639	53	0.01	8	430	220	40	<20	27	<0.01	<10	11	<10	<1	259
Resplit:																													
1	G35006	1.1	1.76	5	55	<5	1.00	3	18	53	835	4.51	<10	1.56	723	180	0.01	8	1580	62	20	<20	38	0.03	<10	39	<10	1	70
Standard:																													
Pb113		11.6	0.25	40	50	<5	1.53	37	2	4	2232	1.07	<10	0.10	1523	69	0.02	8	90	5354	25	<20	78	<0.01	<10	8	10	<1	6957

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
df/5518
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5530

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

10-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07065
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35041	0.53	0.015
2	G35042	0.67	0.020
3	G35043	0.66	0.019
4	G35044	1.03	0.030
5	G35045	0.60	0.017
6	G35046	0.87	0.025
7	G35047	0.85	0.025
8	G35048	0.84	0.024
9	G35049	0.61	0.018
10	G35050	0.58	0.017
11	G35051	1.73	0.050
12	G35052	0.86	0.025
13	G35053	1.25	0.036
14	G35054	0.29	0.008
15	G35055	0.47	0.014
16	G35056	0.44	0.013
17	G35057	0.56	0.016
18	G35058	0.73	0.021
19	G35059	0.76	0.022
20	G35060	0.78	0.023
21	G35061	0.61	0.018
22	G35062	0.48	0.014
23	G35063	0.59	0.017
24	G35064	0.49	0.014
25	G35065	0.91	0.027
26	G35066	1.07	0.031
27	G35067	<0.03	<0.001

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7 - 5530

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G35068	1.08	0.031
29	G35069	1.07	0.031
30	G35070	1.23	0.036
31	G35071	1.09	0.032
32	G35072	1.09	0.032
33	G35073	1.04	0.030
34	G35074	1.18	0.034
35	G35075	0.68	0.020

QC DATA:

Repeat:

1	G35041	0.59	0.017
10	G35050	0.60	0.017
11	G35051	1.57	0.046
13	G35053	1.34	0.039
19	G35059	0.72	0.021
26	G35066	1.16	0.034
28	G35068	1.01	0.029
30	G35070	1.31	0.038
31	G35071	1.11	0.032
32	G35072	1.13	0.033

Resplits:

1	G35041	0.55	0.016

Standard:

OXi54	G35072	1.87	0.055

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
XLS/07

14-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5530

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07065
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35041	1.6	0.49	<5	40	<5	1.80	1	10	56	1089	3.28	<10	0.24	453	17	0.02	5	1600	20	<5	<20	67	0.01	<10	21	<10	1	44
2	G35042	2.2	0.56	<5	55	<5	1.36	2	9	85	1533	3.25	<10	0.32	410	20	0.02	5	1320	20	<5	<20	48	0.01	<10	20	<10	1	54
3	G35043	2.3	0.55	<5	45	<5	1.79	1	10	75	1648	3.56	<10	0.32	539	15	0.01	5	1390	18	<5	<20	58	0.01	<10	21	<10	2	49
4	G35044	2.4	0.39	<5	35	<5	2.40	2	11	72	1885	2.99	<10	0.32	687	16	<0.01	6	1260	16	<5	<20	42	0.01	<10	11	<10	2	27
5	G35045	1.9	0.43	10	55	<5	1.71	<1	8	60	1250	1.83	<10	0.27	564	17	<0.01	4	1610	16	<5	<20	29	<0.01	<10	13	<10	2	29
6	G35046	2.9	0.64	10	45	<5	1.76	1	12	92	1706	3.19	<10	0.41	699	26	<0.01	5	1360	38	<5	<20	43	0.01	<10	18	<10	2	67
7	G35047	2.3	0.67	15	40	<5	1.90	2	11	91	1513	3.04	<10	0.51	851	17	0.01	6	1290	24	5	<20	50	0.01	<10	17	<10	1	61
8	G35048	2.6	0.69	<5	45	<5	1.94	1	10	50	1653	2.87	<10	0.51	815	19	<0.01	4	1510	18	<5	<20	63	0.01	<10	16	<10	2	57
9	G35049	2.1	0.52	<5	60	<5	2.74	2	10	56	1215	3.07	<10	0.29	1013	16	0.02	4	1480	20	<5	<20	102	0.02	<10	20	<10	2	49
10	G35050	1.9	0.49	5	50	<5	1.81	1	11	57	1301	2.77	<10	0.27	816	18	<0.01	5	1530	34	<5	<20	44	0.02	<10	15	<10	2	68
11	G35051	4.5	0.25	20	35	<5	0.99	4	14	181	4930	4.73	<10	0.13	547	17	0.01	10	310	44	<5	<20	25	<0.01	<10	8	<10	<1	95
12	G35052	3.5	0.40	15	25	<5	1.32	1	13	63	2035	4.09	<10	0.19	459	13	0.02	5	1390	44	<5	<20	43	0.01	<10	15	<10	1	44
13	G35053	2.9	0.40	<5	35	<5	1.89	1	17	82	1964	3.94	<10	0.15	591	48	0.01	6	1360	44	<5	<20	72	0.01	<10	14	<10	2	30
14	G35054	0.9	0.37	<5	120	<5	1.28	1	5	63	654	2.49	<10	0.11	355	19	0.03	3	1620	14	<5	<20	63	0.01	<10	24	<10	1	23
15	G35055	2.1	0.38	15	60	<5	1.64	1	10	58	1086	3.16	<10	0.16	503	17	0.02	5	1540	18	<5	<20	53	0.01	<10	25	<10	1	38
16	G35056	2.0	0.49	<5	65	<5	1.42	1	10	64	1067	3.70	<10	0.31	496	14	0.03	5	1340	16	<5	<20	56	0.02	<10	34	<10	1	52
17	G35057	1.8	0.67	10	45	<5	1.34	<1	11	66	1055	3.63	<10	0.53	571	20	0.03	5	1440	14	<5	<20	56	0.02	<10	41	<10	1	70
18	G35058	2.2	0.52	40	45	<5	2.45	2	11	86	1159	3.81	<10	0.35	649	16	0.02	6	1320	32	<5	<20	171	0.02	<10	22	<10	1	41
19	G35059	2.1	0.55	5	40	<5	1.96	1	11	87	1190	3.92	<10	0.35	700	16	0.02	6	1160	28	<5	<20	121	0.02	<10	24	<10	<1	46
20	G35060	3.9	0.52	20	30	<5	0.88	1	10	80	1473	4.57	<10	0.25	477	17	<0.01	7	1270	30	<5	<20	39	0.02	<10	15	<10	<1	48
21	G35061	3.0	0.57	15	30	<5	2.05	1	11	92	1639	3.62	<10	0.38	1066	24	<0.01	5	1130	30	<5	<20	166	0.02	<10	12	<10	2	56
22	G35062	2.1	0.49	20	30	<5	2.38	1	9	101	1405	2.59	<10	0.27	1091	17	0.01	6	1150	20	<5	<20	203	0.01	<10	14	<10	3	36
23	G35063	2.4	0.70	<5	45	<5	2.23	1	9	87	1359	3.60	<10	0.48	1011	19	0.02	6	1290	24	<5	<20	118	0.02	<10	29	<10	5	61
24	G35064	1.9	0.60	<5	40	<5	1.48	1	10	77	1199	4.13	<10	0.47	573	15	0.03	6	1220	16	<5	<20	173	0.02	<10	49	<10	<1	56
25	G35065	3.7	0.74	5	40	<5	1.21	2	14	82	2303	4.36	<10	0.69	543	18	0.03	6	1150	34	<5	<20	90	0.02	<10	58	<10	1	93

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35066	3.8	0.71	<5	45	<5	1.30	3	10	82	2599	3.92	<10	0.57	557	27	0.02	6	1130	36	<5	<20	76	0.02	<10	33	<10	1	184
27	G35067	<0.2	0.96	5	245	<5	0.59	<1	5	94	8	2.10	<10	0.53	516	2	0.12	6	910	14	<5	<20	88	0.10	<10	42	<10	4	46
28	G35068	3.9	0.83	<5	40	<5	0.89	2	10	107	2613	4.03	<10	0.62	589	17	0.01	7	1190	26	<5	<20	39	0.01	<10	30	<10	1	78
29	G35069	3.5	0.97	<5	35	<5	0.65	5	12	110	1702	4.55	<10	0.81	669	17	0.02	6	1110	124	<5	<20	36	0.02	<10	31	<10	<1	121
30	G35070	5.0	0.98	5	45	<5	0.94	1	13	87	3128	4.28	<10	0.77	845	24	0.02	6	1160	52	<5	<20	54	0.02	<10	34	<10	2	111
31	G35071	3.5	0.91	<5	35	<5	0.79	1	10	96	2453	4.16	<10	0.76	613	19	0.03	5	1030	38	<5	<20	53	0.02	<10	42	<10	1	96
32	G35072	3.2	1.09	<5	50	<5	0.85	1	13	84	2211	4.98	<10	0.93	799	16	0.03	6	1190	32	<5	<20	46	0.02	<10	52	<10	<1	131
33	G35073	3.6	1.05	55	50	<5	0.69	3	15	52	3339	3.72	20	0.44	256	194	0.03	14	400	120	35	<20	24	0.02	<10	39	<10	5	160
34	G35074	3.5	1.00	<5	35	<5	0.56	1	11	85	2119	4.32	<10	0.83	543	21	0.03	6	1180	34	<5	<20	37	0.02	<10	41	<10	1	108
35	G35075	2.8	0.98	<5	85	<5	0.84	2	10	90	1524	3.82	<10	0.77	635	20	0.04	5	1250	34	<5	<20	51	0.02	<10	47	<10	1	103
QC DATA:																													
Repeat:																													
1	G35041	1.6	0.48	<5	40	<5	1.74	<1	10	55	1042	3.14	<10	0.23	439	16	0.02	5	1540	18	<5	<20	70	0.01	<10	20	<10	1	41
10	G35050	1.8	0.47	<5	50	<5	1.75	2	11	56	1219	2.70	<10	0.26	790	20	<0.01	4	1480	34	<5	<20	40	0.01	<10	14	<10	2	69
19	G35059	2.1	0.55	<5	50	<5	1.94	2	11	87	1166	3.87	<10	0.34	690	16	0.02	5	1120	28	<5	<20	122	0.02	<10	23	<10	1	46
Resplit:																													
1	G35041	1.6	0.51	<5	40	<5	1.77	1	10	51	1077	3.20	<10	0.27	475	17	0.02	5	1620	24	<5	<20	68	0.02	<10	21	<10	1	54
Standard:																													
Pb113		10.9	0.22	50	50	<5	1.58	35	<1	4	2240	1.08	<10	0.09	1390	72	0.02	3	70	5598	25	<20	81	<0.01	<10	6	10	<1	6930

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
dl/5530S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5531

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

5-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07066
Submitted by: Mike Savell

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37061	0.40	0.012
2	G37062	0.18	0.005
3	G37063	0.22	0.006
4	G37064	0.27	0.008
5	G37065	0.14	0.004
6	G37066	0.20	0.006
7	G37067	0.20	0.006
8	G37068	0.34	0.010
9	G37069	0.22	0.006
10	G37070	0.17	0.005
11	G37071	0.43	0.013
12	G37072	0.30	0.009
13	G37073	0.44	0.013
14	G37074	<0.03	<0.001
15	G37075	0.21	0.006
16	G37076	0.18	0.005
17	G37077	0.36	0.010
18	G37078	0.26	0.008
19	G37079	0.19	0.006
20	G37080	0.14	0.004
21	G37081	0.11	0.003
22	G37082	0.19	0.006
23	G37083	0.17	0.005
24	G37084	0.10	0.003
25	G37085	0.09	0.003
26	G37086	0.13	0.004
27	G37087	0.12	0.003

Seabridge Gold Inc. AS7 - 5531

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G37088	0.14	0.004
29	G37089	0.94	0.027
30	G37090	0.18	0.005
31	G37091	0.17	0.005
32	G37092	0.09	0.003
33	G37093	0.12	0.003
34	G37094	0.16	0.005
35	G37095	0.09	0.003

QC DATA:

Repeat:

1	G37061	0.38	0.011
10	G37070	0.18	0.005
19	G37079	0.19	0.006

Resplits:

1	G37061	0.37	0.011

Standard:

OXI54		1.85	0.054

AU: 30g FA/AA-Finish

JJ/jl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

4-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5531

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07066
Submitted by: Mike Savell

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37061	0.9	1.21	25	45	<5	2.59	<1	14	72	691	3.62	<10	0.95	1098	62	0.04	5	1350	34	10	<20	153	0.09	<10	55	<10	5	69
2	G37062	0.5	1.20	<5	80	<5	2.30	1	16	78	568	3.92	<10	0.87	1101	38	0.05	5	1380	22	<5	<20	141	0.10	<10	61	<10	5	74
3	G37063	0.8	1.32	<5	70	<5	2.00	1	16	70	581	3.77	<10	1.04	1079	29	0.05	5	1530	24	10	<20	109	0.09	<10	63	<10	5	99
4	G37064	0.7	1.18	20	60	<5	3.43	<1	13	64	522	3.59	<10	0.91	1535	37	0.04	5	1460	20	5	<20	212	0.09	<10	47	<10	5	90
5	G37065	0.8	1.38	10	115	<5	2.64	<1	13	60	604	3.83	<10	1.06	1321	50	0.05	4	1450	22	10	<20	178	0.09	<10	61	<10	4	106
6	G37066	1.0	1.38	5	85	<5	1.70	<1	17	96	993	3.85	<10	1.11	1007	170	0.05	5	1210	30	10	<20	132	0.09	<10	71	<10	6	77
7	G37067	0.8	1.31	5	80	<5	2.94	1	15	53	581	3.84	<10	1.00	1316	28	0.05	5	1480	30	10	<20	198	0.08	<10	71	<10	4	98
8	G37068	4.6	1.01	30	50	<5	1.78	2	15	97	1198	4.00	<10	0.64	1105	64	0.02	5	1370	196	<5	<20	84	0.06	<10	38	<10	4	159
9	G37069	4.7	0.69	15	40	<5	2.17	6	14	97	606	4.45	<10	0.37	1017	53	0.01	5	1320	100	<5	<20	82	0.06	<10	25	<10	4	336
10	G37070	1.5	1.15	30	75	<5	3.01	<1	13	125	612	2.91	<10	0.81	1223	154	0.02	5	1420	26	5	<20	116	0.06	<10	33	<10	6	94
11	G37071	2.2	1.08	25	65	<5	3.32	1	11	105	1300	2.85	<10	0.78	1135	171	0.01	6	1450	24	15	<20	113	0.04	<10	32	<10	8	81
12	G37072	1.5	1.22	25	75	<5	2.37	<1	14	61	884	3.08	<10	0.95	1069	110	0.02	4	1750	28	5	<20	105	0.05	<10	37	<10	8	107
13	G37073	1.6	1.14	20	80	<5	3.06	1	11	73	1078	2.88	<10	0.88	1041	61	0.03	5	1370	30	15	<20	139	0.07	<10	39	<10	7	67
14	G37074	<0.2	1.09	25	250	15	0.63	<1	7	89	6	2.30	<10	0.61	557	3	0.12	5	970	20	<5	<20	83	0.13	<10	49	<10	3	45
15	G37075	1.1	1.44	5	80	<5	2.03	<1	14	56	733	3.97	<10	1.10	1005	44	0.04	4	1490	28	10	<20	132	0.08	<10	60	<10	5	82
16	G37076	1.0	1.42	10	45	<5	2.29	1	17	69	726	4.16	<10	1.15	1084	52	0.03	6	1530	30	15	<20	137	0.08	<10	54	<10	6	82
17	G37077	1.7	0.74	20	50	<5	7.68	4	12	75	722	3.72	<10	0.45	1933	81	0.02	4	1130	80	<5	<20	293	0.07	<10	24	<10	10	209
18	G37078	2.3	0.86	25	35	<5	5.40	35	16	99	1132	4.59	<10	0.61	1606	117	0.02	7	1100	118	5	<20	253	0.06	<10	32	<10	4	1511
19	G37079	1.6	0.99	30	50	<5	4.43	<1	14	94	998	3.13	<10	0.65	1476	41	0.01	5	1360	64	5	<20	230	0.07	<10	33	<10	6	86
20	G37080	0.9	1.22	35	60	<5	3.91	<1	15	86	579	3.34	<10	0.93	1530	144	0.02	5	1550	54	10	<20	191	0.07	<10	40	<10	7	129
21	G37081	0.4	1.01	20	50	<5	4.38	<1	11	70	224	3.09	<10	0.69	1350	28	0.02	4	1540	22	<5	<20	182	0.07	<10	33	<10	7	64
22	G37082	0.5	1.29	30	55	<5	3.24	1	15	59	390	3.73	<10	0.93	1264	60	0.03	6	1650	30	20	<20	181	0.07	<10	51	<10	6	79
23	G37083	0.7	1.37	25	50	<5	2.57	<1	16	56	539	4.16	<10	0.99	1166	22	0.04	6	1650	28	15	<20	158	0.09	<10	54	<10	4	83
24	G37084	0.7	1.22	15	40	<5	2.91	1	14	73	392	3.49	<10	0.96	1014	113	0.03	5	1590	26	10	<20	173	0.08	<10	42	<10	6	68
25	G37085	0.4	1.34	20	60	<5	2.36	<1	12	76	418	3.37	<10	1.06	910	24	0.05	5	1590	24	10	<20	147	0.08	<10	53	<10	7	74

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37086	0.7	1.31	15	65	<5	2.60	<1	15	81	529	3.38	<10	1.04	879	147	0.04	4	1550	28	10	<20	137	0.08	<10	50	<10	8	62
27	G37087	0.6	1.46	20	80	<5	2.71	<1	13	54	369	3.47	<10	1.11	1010	20	0.03	5	1760	26	15	<20	147	0.07	<10	48	<10	5	72
28	G37088	2.5	0.98	40	55	<5	4.00	2	11	112	625	3.12	<10	0.65	1046	81	0.02	4	1290	90	<5	<20	130	0.07	<10	31	<10	10	146
29	G37089	<0.2	0.98	1545	80	20	1.02	5	33	25	55	4.74	<10	2.15	696	1	0.22	110	1210	26	20	<20	52	0.12	<10	26	<10	13	69
30	G37090	1.4	1.03	25	55	<5	2.83	1	17	78	825	3.53	<10	0.74	901	105	0.02	5	1530	44	<5	<20	99	0.07	<10	33	<10	8	64
31	G37091	1.0	1.16	25	45	<5	3.57	<1	17	77	762	3.97	<10	0.88	1143	58	0.03	4	1470	34	<5	<20	148	0.08	<10	39	<10	8	60
32	G37092	0.6	1.48	25	65	<5	1.86	<1	14	52	473	3.92	<10	1.23	1029	51	0.03	5	1710	34	20	<20	81	0.08	<10	48	<10	8	74
33	G37093	0.9	1.33	25	40	<5	1.75	1	19	76	640	4.27	<10	1.00	866	24	0.03	8	1540	72	20	<20	108	0.07	<10	41	<10	7	58
34	G37094	0.9	1.39	30	50	<5	2.19	<1	19	54	624	4.15	<10	1.07	855	35	0.04	4	1670	34	10	<20	104	0.09	<10	50	<10	7	80
35	G37095	1.1	1.34	25	50	<5	2.24	<1	18	63	756	3.97	<10	1.07	788	103	0.05	4	1650	44	10	<20	126	0.10	<10	59	<10	7	84
QC DATA:																													
Repeat:																													
1	G37061	0.9	1.18	25	40	<5	2.63	1	15	71	677	3.72	<10	0.93	1112	61	0.04	5	1410	36	10	<20	151	0.08	<10	54	<10	5	74
10	G37070	1.5	1.08	35	70	<5	3.02	<1	13	122	606	2.90	<10	0.79	1215	163	0.01	5	1440	28	10	<20	113	0.05	<10	31	<10	6	100
19	G37079	1.7	1.02	35	50	<5	4.61	<1	15	98	1064	3.33	<10	0.69	1521	47	0.01	5	1420	74	10	<20	249	0.07	<10	34	<10	7	91
Resplit:																													
1	G37061	1.1	1.26	25	40	<5	2.73	1	19	71	681	3.66	<10	0.96	1135	66	0.04	6	1360	32	15	<20	164	0.08	<10	56	<10	5	72
Standard:																													
Pb113		11.6	0.29	40	65	<5	1.64	42	3	6	2357	1.19	<10	0.11	1558	60	0.02	2	90	5534	25	<20	87	0.01	<10	9	10	<1	7029

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5531S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5532

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

5-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07067
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37096	0.10	0.003
2	G37097	0.06	0.002
3	G37098	0.16	0.005
4	G37099	0.11	0.003
5	G37100	0.11	0.003
6	G37101	0.72	0.021
7	G37102	0.97	0.028
8	G37103	0.11	0.003
9	G37104	0.06	0.002
10	G37105	0.06	0.002
11	G37106	0.08	0.002
12	G37107	0.16	0.005
13	G37108	0.13	0.004
14	G37109	0.11	0.003
15	G37110	0.82	0.024
16	G37111	0.74	0.022
17	G37112	0.72	0.021
18	G37113	0.72	0.021
19	G37114	0.97	0.028
20	G37115	0.66	0.019
21	G37116	0.77	0.022
22	G37117	0.64	0.019
23	G37118	0.73	0.021
24	G37119	0.66	0.019
25	G37120	0.87	0.025

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AK7-5532 5-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	G37121	0.53	0.015
27	G37122	<0.03	<0.001
28	G37123	0.38	0.011
29	G37124	0.26	0.008
30	G37125	0.29	0.008
31	G37126	0.35	0.010
32	G37127	0.28	0.008
33	G37128	0.46	0.013
34	G37129	0.41	0.012
35	G37130	0.36	0.010

QC DATA:

Repeat:

1	G37096	0.10	0.003
10	G37105	0.06	0.002
19	G37114	0.83	0.024

Resplits:

1	G37096	0.11	0.003

Standard:

OXI54		1.83	0.053

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO-TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

5-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5532

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07067
Submitted by: Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37096	1.6	1.23	30	45	<5	2.52	<1	19	86	789	3.56	<10	0.83	833	88	0.03	5	1660	44	15	<20	119	0.09	<10	43	<10	9	78
2	G37097	1.2	1.32	20	60	<5	2.23	<1	16	63	521	3.43	<10	0.98	873	44	0.02	4	1730	36	10	<20	98	0.09	<10	42	<10	8	116
3	G37098	4.9	1.21	25	50	<5	3.54	3	16	70	745	4.11	<10	0.81	1150	71	0.03	5	1620	96	10	<20	137	0.09	<10	39	<10	7	182
4	G37099	3.1	1.20	20	50	<5	2.25	<1	15	71	535	3.54	<10	0.84	869	62	0.03	5	1660	38	10	<20	96	0.09	<10	43	<10	7	93
5	G37100	2.3	1.39	25	70	<5	2.06	<1	16	58	472	3.51	<10	1.05	874	64	0.03	6	1740	34	10	<20	87	0.09	<10	42	<10	8	102
6	G37101	3.2	1.09	40	70	<5	2.70	6	13	74	749	3.31	<10	0.71	959	93	0.02	4	1770	118	5	<20	94	0.09	<10	32	<10	8	401
7	G37102	3.7	1.22	70	65	<5	0.78	4	18	61	3270	3.91	20	0.52	287	224	0.03	14	410	150	40	<20	29	0.04	<10	46	<10	5	150
8	G37103	1.7	1.21	25	60	<5	2.03	1	15	74	427	3.33	<10	0.90	1033	29	0.02	8	1760	32	20	<20	69	0.08	<10	39	<10	7	115
9	G37104	1.1	1.25	35	65	<5	1.71	<1	12	66	433	2.92	<10	0.99	901	22	0.03	5	1840	30	5	<20	59	0.09	<10	48	<10	8	109
10	G37105	1.4	1.12	25	50	<5	1.99	<1	17	65	497	3.14	<10	0.80	743	36	0.03	5	1730	34	10	<20	75	0.09	<10	39	<10	8	98
11	G37106	1.8	1.32	30	40	<5	2.28	<1	18	65	463	3.70	<10	1.00	860	54	0.04	6	1800	42	10	<20	89	0.10	<10	45	<10	8	137
12	G37107	1.6	1.19	25	45	<5	1.85	<1	17	81	523	4.14	<10	0.87	709	38	0.04	5	1530	40	<5	<20	80	0.10	<10	44	<10	5	122
13	G37108	1.3	1.41	20	60	<5	2.60	1	17	52	533	4.75	<10	1.12	792	105	0.05	5	1640	40	10	<20	186	0.11	<10	65	<10	7	70
14	G37109	0.8	1.19	15	40	<5	2.48	<1	14	73	329	3.60	<10	0.89	714	34	0.04	5	1480	30	5	<20	168	0.10	<10	48	<10	5	63
15	G37110	3.3	1.23	20	215	<5	1.54	1	13	123	2143	4.82	<10	0.72	1129	27	0.01	6	1140	36	5	<20	155	0.03	<10	37	<10	3	97
16	G37111	3.2	1.15	45	55	<5	0.69	1	14	136	1695	4.81	<10	0.67	994	34	<0.01	8	1260	44	10	<20	45	0.03	<10	23	<10	3	113
17	G37112	2.9	0.90	40	40	<5	1.07	3	12	152	1731	4.60	<10	0.57	985	24	<0.01	7	1090	52	5	<20	63	0.02	<10	20	<10	3	166
18	G37113	3.2	1.42	30	60	<5	0.50	3	14	142	1971	5.01	<10	0.87	569	26	<0.01	8	1010	46	10	<20	43	0.02	<10	35	<10	2	224
19	G37114	10.5	1.22	35	60	<5	0.80	7	14	165	2202	4.88	<10	0.72	721	33	0.01	7	1100	136	10	<20	80	0.02	<10	32	<10	2	501
20	G37115	2.7	1.35	25	55	<5	0.64	3	13	157	1815	4.74	<10	0.91	882	25	0.01	8	1070	48	10	<20	73	0.02	<10	41	<10	2	223
21	G37116	2.8	1.13	30	60	<5	0.59	5	13	153	2152	5.02	<10	0.67	671	22	0.02	6	1020	40	<5	<20	76	0.02	<10	41	<10	2	236
22	G37117	2.2	1.26	30	60	<5	0.50	4	12	146	1280	5.03	<10	0.76	568	18	0.01	6	1140	38	10	<20	48	0.02	<10	36	<10	<1	234
23	G37118	7.4	0.43	55	45	<5	0.12	2	10	153	1263	5.44	<10	0.04	94	30	<0.01	5	900	44	<5	<20	6	0.02	<10	11	<10	<1	54
24	G37119	3.1	1.08	25	70	<5	0.49	<1	11	165	2283	4.12	<10	0.59	558	18	0.01	6	680	34	<5	<20	54	0.02	<10	27	<10	3	89
25	G37120	2.3	1.03	10	75	<5	1.05	2	12	134	2372	4.59	<10	0.60	746	29	0.02	5	830	32	<5	<20	113	0.02	<10	32	<10	3	138

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37121	2.2	0.91	20	120	<5	1.49	2	11	142	1490	4.07	<10	0.47	910	23	0.02	7	890	30	5	<20	167	0.03	<10	28	<10	5	120
27	G37122	<0.2	1.18	25	265	20	0.51	<1	8	99	8	2.10	<10	0.63	521	2	0.12	7	900	18	5	<20	94	0.14	<10	51	<10	4	48
28	G37123	1.5	0.94	15	150	<5	1.47	3	12	116	1136	4.37	<10	0.52	943	25	0.03	5	1010	32	<5	<20	169	0.03	<10	36	<10	4	150
29	G37124	1.1	0.98	15	280	<5	2.08	3	9	110	783	4.37	<10	0.58	1199	26	0.03	8	1030	42	20	<20	255	0.04	<10	50	<10	5	185
30	G37125	1.2	0.93	10	215	<5	1.91	3	10	91	832	4.38	<10	0.57	1139	22	0.03	5	1020	40	10	<20	220	0.04	<10	47	<10	4	195
31	G37126	1.5	0.99	25	180	<5	0.96	3	10	128	1144	3.85	<10	0.55	786	15	0.02	6	900	36	5	<20	103	0.03	<10	34	<10	4	180
32	G37127	1.3	0.85	20	165	<5	1.35	4	11	111	773	4.40	<10	0.40	848	17	0.02	5	1060	46	<5	<20	139	0.03	<10	42	<10	4	209
33	G37128	1.6	1.05	25	200	<5	0.42	<1	10	121	1086	4.05	<10	0.53	683	16	0.02	6	1060	38	<5	<20	29	0.03	<10	33	<10	6	135
34	G37129	1.9	0.97	30	165	<5	0.50	1	8	92	1128	2.94	<10	0.48	586	16	0.01	4	1130	34	<5	<20	26	0.03	<10	20	<10	5	135
35	G37130	1.6	0.89	25	130	<5	1.51	4	10	103	894	2.96	<10	0.41	876	28	0.02	4	1020	56	<5	<20	100	0.06	<10	21	<10	6	179
QC DATA:																													
Repeat:																													
1	G37096	1.5	1.15	35	45	<5	2.46	<1	18	82	761	3.47	<10	0.79	811	87	0.03	5	1620	42	10	<20	115	0.09	<10	40	<10	8	77
10	G37105	1.4	1.11	25	45	<5	1.98	<1	17	64	507	3.15	<10	0.81	748	37	0.03	7	1750	34	20	<20	75	0.07	<10	40	<10	8	97
19	G37114	10.4	1.19	30	55	<5	0.80	9	14	161	2258	4.87	<10	0.73	724	30	0.01	8	1080	136	10	<20	83	0.02	<10	31	<10	2	499
Resplit:																													
1	G37096	1.4	1.17	25	50	<5	2.41	1	16	85	706	3.61	<10	0.84	818	89	0.03	7	1670	42	15	<20	113	0.07	<10	40	<10	8	78
Standard:																													
Pb113		11.0	0.30	65	50	<5	1.75	45	3	6	2311	1.20	<10	0.12	1563	71	0.02	2	70	5480	15	<20	77	0.01	<10	10	10	<1	7119

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5531
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5533

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

10-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07068
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35076	0.73	0.021
2	G35077	1.08	0.031
3	G35078	0.83	0.024
4	G35079	1.17	0.034
5	G35080	0.76	0.022
6	G35081	0.90	0.026
7	G35082	1.35	0.039
8	G35083	1.21	0.035
9	G35084	0.80	0.023
10	G35085	0.70	0.020
11	G35086	0.78	0.023
12	G35087	0.77	0.022
13	G35088	0.69	0.020
14	G35089	1.29	0.038
15	G35090	1.87	0.055
16	G35091	1.21	0.035
17	G35092	1.18	0.034
18	G35093	1.33	0.039
19	G35094	1.16	0.034
20	G35095	<0.03	<0.001
21	G35096	1.66	0.048
22	G35097	2.67	0.078
23	G35098	1.39	0.041
24	G35099	1.69	0.049
25	G35100	1.61	0.047
26	G35101	0.82	0.024
27	G35102	0.84	0.024

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5533 10-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G35103	0.80	0.023
29	G35104	1.32	0.038
30	G35105	1.25	0.036
31	G35106	0.98	0.029
32	G35107	0.93	0.027
33	G35108	1.05	0.031
34	G35109	1.06	0.031
35	G35110	1.30	0.038

QC DATA:

Repeat:

1	G35076	0.77	0.022
4	G35079	1.11	0.032
10	G35085	0.67	0.020
18	G35093	1.22	0.036
19	G35094	1.26	0.037
28	G35103	0.86	0.025
29	G35104	1.40	0.041
30	G35105	1.39	0.041

Resplits:

1	G35076	0.82	0.024
35	G35110	1.25	0.036

Standard:

Oxi54		1.88	0.055

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

14-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5533

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07068
Submitted by: Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35076	2.6	1.10	<5	85	<5	0.49	1	10	88	1540	4.08	<10	0.90	613	20	0.04	4	1270	24	<5	<20	42	0.02	<10	50	<10	<1	137
2	G35077	5.7	0.86	<5	40	<5	0.88	3	19	77	1530	6.74	<10	0.69	800	23	0.02	8	1030	224	<5	<20	48	0.02	<10	29	<10	<1	111
3	G35078	2.8	1.11	5	30	<5	0.44	1	11	83	1480	4.22	<10	0.90	628	27	0.02	5	1330	24	<5	<20	27	0.02	<10	40	<10	<1	116
4	G35079	3.8	0.86	15	30	<5	0.73	1	12	97	1754	4.35	<10	0.62	701	19	0.01	7	1210	30	<5	<20	31	0.02	<10	22	<10	<1	103
5	G35080	4.2	0.42	25	25	<5	0.85	1	11	136	1895	3.42	<10	0.22	486	14	0.01	6	840	30	<5	<20	36	0.01	<10	10	<10	<1	53
6	G35081	3.2	0.92	<5	40	<5	1.49	1	11	95	1939	4.57	<10	0.73	870	13	0.02	6	1180	22	<5	<20	83	0.02	<10	32	<10	<1	69
7	G35082	5.1	0.76	<5	35	<5	0.55	2	12	117	3254	5.10	<10	0.56	529	13	0.02	6	720	24	<5	<20	43	0.02	<10	31	<10	<1	65
8	G35083	5.3	0.74	10	30	<5	1.29	2	14	104	2479	4.84	<10	0.56	760	16	0.02	8	940	38	5	<20	132	0.01	<10	31	<10	1	85
9	G35084	3.6	1.09	15	45	<5	2.31	2	11	70	1533	4.79	<10	1.08	1338	16	0.05	6	1310	42	<5	<20	724	0.03	<10	64	<10	1	183
10	G35085	3.4	0.96	<5	40	<5	2.67	2	10	73	1548	4.04	<10	0.85	1589	16	0.04	5	1210	36	<5	<20	178	0.03	<10	57	<10	4	136
11	G35086	3.0	1.06	5	45	<5	0.85	2	11	67	1355	4.12	<10	0.88	857	17	0.04	4	1340	32	5	<20	68	0.02	<10	46	<10	1	134
12	G35087	3.8	0.94	<5	75	<5	0.79	2	12	85	1520	4.30	<10	0.70	758	21	0.02	5	1180	50	<5	<20	51	0.02	<10	31	<10	<1	115
13	G35088	3.6	0.77	15	30	<5	1.20	2	13	93	1393	4.83	<10	0.56	793	16	0.03	6	1110	52	<5	<20	63	0.02	<10	32	<10	<1	96
14	G35089	5.3	0.71	10	35	<5	1.05	3	16	90	2762	4.26	<10	0.44	677	25	0.01	5	1140	56	<5	<20	59	0.02	<10	20	<10	<1	108
15	G35090	3.9	0.98	25	40	<5	1.00	2	21	55	8642	4.10	10	0.54	196	562	0.04	64	260	62	20	<20	44	0.02	<10	40	<10	5	80
16	G35091	4.3	0.73	<5	30	<5	1.11	2	11	72	1933	4.02	<10	0.49	718	13	0.01	4	970	38	<5	<20	59	0.02	<10	23	<10	<1	82
17	G35092	4.0	0.84	<5	25	<5	1.27	2	11	111	2060	4.19	<10	0.59	688	16	0.01	7	1010	36	<5	<20	49	0.01	<10	24	<10	<1	80
18	G35093	13.5	0.81	15	30	<5	2.07	2	9	72	1970	3.82	<10	0.65	702	17	0.02	5	1180	54	<5	<20	222	0.02	<10	28	<10	<1	100
19	G35094	4.7	0.80	5	30	<5	1.72	2	10	98	2705	4.65	<10	0.72	421	23	0.03	6	1070	38	<5	<20	188	0.02	<10	42	<10	<1	91
20	G35095	<0.2	0.98	5	225	5	0.53	<1	5	98	7	2.06	<10	0.50	506	3	0.08	6	900	12	<5	<20	60	0.09	<10	41	<10	3	47
21	G35096	5.0	0.82	10	35	<5	1.18	2	12	95	2290	5.24	<10	0.67	507	19	0.02	6	1120	48	<5	<20	66	0.02	<10	38	<10	<1	84
22	G35097	4.8	0.59	165	35	<5	1.74	2	10	81	2048	4.74	<10	0.46	577	21	0.02	6	1190	32	20	<20	77	0.02	<10	28	<10	<1	75
23	G35098	3.1	0.31	85	25	<5	1.37	2	9	76	1568	4.05	<10	0.18	689	16	0.01	5	1260	18	<5	<20	76	0.02	<10	11	<10	<1	36
24	G35099	4.6	0.41	35	25	<5	2.16	2	11	113	2965	4.20	<10	0.30	599	16	0.01	5	960	26	<5	<20	134	0.01	<10	15	<10	<1	43
25	G35100	5.0	0.33	<5	30	<5	1.58	3	14	106	3645	4.72	<10	0.23	705	14	0.01	6	930	64	<5	<20	127	0.01	<10	14	<10	<1	141

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35101	2.7	0.41	<5	30	<5	3.21	2	8	89	1510	3.93	<10	0.20	628	13	0.02	5	1220	52	<5	<20	178	0.02	<10	28	<10	<1	64
27	G35102	3.4	0.38	<5	40	<5	3.26	2	10	93	1917	4.26	<10	0.20	594	11	0.02	4	1000	50	<5	<20	173	0.02	<10	28	<10	<1	76
28	G35103	3.8	0.78	<5	40	<5	4.90	6	14	68	1662	4.56	<10	0.79	2037	13	0.02	6	810	64	<5	<20	152	0.04	<10	37	<10	<1	331
29	G35104	4.6	0.69	5	35	<5	2.50	3	12	77	2397	4.43	<10	0.63	816	17	0.02	8	1170	52	10	<20	120	0.01	<10	26	<10	<1	157
30	G35105	4.1	0.69	<5	35	<5	2.09	2	12	92	2680	4.83	<10	0.61	559	13	0.02	5	1050	56	<5	<20	137	0.02	<10	39	<10	<1	111
31	G35106	4.5	0.80	<5	40	<5	1.96	3	13	116	2635	6.08	<10	0.75	784	18	0.02	7	930	56	<5	<20	133	0.02	<10	54	<10	<1	149
32	G35107	3.7	0.75	<5	35	<5	2.50	5	13	116	2243	4.97	<10	0.65	774	19	0.02	6	990	66	<5	<20	191	0.02	<10	43	<10	<1	344
33	G35108	4.0	0.60	10	25	<5	2.42	3	11	74	2105	4.01	<10	0.47	838	18	0.01	5	1230	94	<5	<20	130	0.02	<10	22	<10	<1	218
34	G35109	2.8	0.49	<5	30	<5	2.41	2	10	88	1916	4.81	<10	0.39	596	17	0.01	6	1260	30	<5	<20	139	0.02	<10	27	<10	<1	101
35	G35110	5.2	0.22	40	30	<5	1.11	3	15	118	3066	5.68	<10	<0.01	367	13	0.01	7	800	54	<5	<20	67	0.01	<10	10	<10	<1	89
QC DATA:																													
Repeat:																													
1	G35076	2.7	1.14	<5	90	<5	0.50	1	10	92	1594	4.22	<10	0.93	633	23	0.04	6	1350	24	<5	<20	46	0.02	<10	52	<10	<1	141
10	G35085	3.3	0.94	5	50	<5	2.64	2	11	73	1494	4.02	<10	0.83	1567	20	0.04	8	1220	38	5	<20	177	0.02	<10	57	<10	4	138
19	G35094	4.5	0.80	10	30	<5	1.71	1	10	100	2647	4.65	<10	0.71	418	22	0.03	5	1070	38	<5	<20	188	0.02	<10	43	<10	<1	92
Resplit:																													
1	G35076	2.9	1.06	5	75	<5	0.53	1	11	82	1551	4.06	<10	0.86	637	21	0.03	6	1260	24	<5	<20	45	0.02	<10	46	<10	<1	138
Standard:																													
Pb113		11.1	0.22	50	50	<5	1.58	35	<1	4	2189	1.03	<10	0.08	1452	69	0.02	3	90	5470	20	<20	78	<0.01	<10	5	10	<1	6926

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5530S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5537

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

21-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07069
Submitted by: Tim Todd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37131	0.41	0.012
2	G37132	0.29	0.008
3	G37133	0.23	0.007
4	G37134	0.34	0.010
5	G37135	0.48	0.014
6	G37136	0.35	0.010
7	G37137	<0.03	<0.001
8	G37138	<0.03	<0.001
9	G37139	0.30	0.009
10	G37140	<0.03	<0.001
11	G37141	0.28	0.008
12	G37142	0.37	0.011
13	G37143	0.41	0.012
14	G37144	0.28	0.008
15	G37145	0.44	0.013
16	G37146	0.20	0.006
17	G37147	0.30	0.009
18	G37148	0.28	0.008
19	G37149	0.33	0.010
20	G37150	0.44	0.013
21	G37151	0.66	0.019
22	G37152	0.38	0.011
23	G37153	0.69	0.020
24	G37154	0.82	0.024
25	G37155	0.26	0.008
26	G37156	0.37	0.011
27	G37157	0.39	0.011
28	G37158	0.42	0.012

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5537 21-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G37159	0.32	0.009
30	G37160	0.42	0.012
31	G37161	0.64	0.019
32	G37162	0.42	0.012
33	G37163	0.64	0.019
34	G37164	0.66	0.019
35	G37165	0.72	0.021
QC DATA:			
Repeat:			
1	G37131	0.42	0.012
11	G37141	0.26	0.008
19	G37149	0.35	0.010
Resplits:			
1	G37131	0.44	0.013
Standard:			
SI25		1.78	0.052

AU: 30g FA/AA-Finish

JJ/jl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

21-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5537

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07069
Submitted by: Tim Todd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37131	5.7	0.76	20	75	<5	1.41	4	10	121	1097	2.83	<10	0.38	728	23	<0.01	6	910	60	<5	<20	72	0.05	<10	16	<10	3	245
2	G37132	2.0	0.80	10	70	<5	0.83	3	11	93	1111	3.21	<10	0.47	638	26	0.01	5	990	38	<5	<20	35	0.06	<10	20	<10	4	138
3	G37133	1.5	0.80	15	175	<5	0.70	2	10	109	968	3.78	<10	0.48	666	37	0.03	5	980	32	<5	<20	47	0.08	<10	39	<10	4	151
4	G37134	1.7	0.92	10	130	<5	0.32	<1	10	94	1090	3.47	<10	0.60	650	26	0.03	5	940	32	<5	<20	24	0.08	<10	31	<10	5	114
5	G37135	2.3	0.89	10	80	<5	0.30	1	10	107	1552	3.47	<10	0.60	643	24	0.02	8	940	26	<5	<20	19	0.07	<10	25	<10	4	102
6	G37136	2.1	1.09	15	215	<5	0.52	<1	11	82	1218	3.56	<10	0.83	697	29	0.04	5	980	32	<5	<20	33	0.10	<10	42	<10	5	117
7	G37137	<0.2	3.70	35	635	<5	3.07	<1	39	174	409	5.91	<10	4.51	1356	7	0.02	103	740	50	20	<20	123	0.24	<10	143	<10	11	125
8	G37138	<0.2	3.74	45	790	20	2.14	<1	39	157	106	5.94	<10	4.58	1216	7	0.02	101	730	52	25	<20	114	0.22	<10	140	<10	10	95
9	G37139	1.7	1.34	20	130	<5	0.79	<1	14	99	1207	3.77	<10	1.09	1033	44	0.02	20	980	36	5	<20	26	0.10	<10	37	<10	7	154
10	G37140	<0.2	0.99	15	245	25	0.64	<1	7	127	7	2.22	<10	0.55	539	2	0.12	7	950	20	5	<20	92	0.14	<10	45	<10	5	49
11	G37141	1.3	1.16	20	115	<5	1.53	2	10	69	930	4.07	<10	0.76	1269	21	<0.01	9	1100	28	15	<20	42	0.07	<10	36	<10	5	121
12	G37142	2.1	0.83	10	130	<5	1.56	1	9	76	1126	2.60	<10	0.47	984	20	<0.01	5	1080	34	5	<20	48	0.07	<10	15	<10	5	107
13	G37143	1.9	0.79	<5	190	<5	1.76	1	9	83	1272	3.16	<10	0.44	964	20	<0.01	6	1130	34	<5	<20	66	0.08	<10	25	<10	8	92
14	G37144	1.1	0.71	15	430	<5	4.06	<1	7	86	897	2.75	<10	0.39	1300	14	0.02	<1	1010	24	<5	<20	218	0.11	<10	22	<10	5	83
15	G37145	2.2	0.87	20	120	<5	1.74	1	12	86	1694	3.66	<10	0.51	871	22	0.01	5	1030	26	<5	<20	69	0.08	<10	23	<10	6	97
16	G37146	1.2	0.66	10	225	<5	1.88	3	9	70	789	2.78	<10	0.33	874	19	<0.01	4	1150	30	<5	<20	73	0.08	<10	23	<10	6	152
17	G37147	3.0	1.12	40	40	<5	0.99	2	21	60	2699	3.50	20	0.59	192	188	0.03	9	500	58	5	<20	49	0.06	<10	45	<10	6	268
18	G37148	1.5	0.88	20	240	<5	2.12	<1	8	84	936	2.65	<10	0.48	976	20	<0.01	5	1110	30	<5	<20	91	0.09	<10	21	<10	6	118
19	G37149	1.7	0.84	15	165	<5	2.34	1	9	78	1157	3.45	<10	0.50	988	19	0.02	4	1050	30	<5	<20	126	0.08	<10	29	<10	5	115
20	G37150	2.1	0.89	15	95	<5	2.23	<1	10	86	1516	3.16	<10	0.56	948	24	0.01	5	980	24	10	<20	124	0.07	<10	25	<10	5	85
21	G37151	2.5	0.89	5	60	<5	1.82	<1	11	87	1935	3.76	<10	0.60	725	21	0.02	4	990	24	<5	<20	129	0.08	<10	28	<10	6	67
22	G37152	1.5	0.85	15	225	<5	1.98	<1	9	93	1173	3.23	<10	0.56	844	29	0.02	6	1040	24	<5	<20	222	0.07	<10	30	<10	6	84
23	G37153	1.8	3.30	30	80	<5	1.01	2	23	101	1467	7.80	<10	2.53	2022	98	<0.01	10	1620	78	10	<20	79	0.07	<10	140	<10	<1	425
24	G37154	3.3	2.17	40	35	<5	0.65	5	27	83	1540	6.80	<10	1.70	1277	103	0.01	11	1960	202	10	<20	21	0.05	<10	81	<10	<1	601
25	G37155	1.2	2.38	30	45	<5	0.70	<1	17	88	617	5.12	<10	2.02	1192	70	0.01	7	2010	174	10	<20	26	0.04	<10	76	<10	<1	516

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37156	1.5	2.66	20	45	<5	0.78	1	21	88	904	5.91	<10	2.27	1189	51	0.01	7	2040	106	5	<20	35	0.05	<10	93	<10	<1	352
27	G37157	1.2	2.71	40	55	<5	0.90	1	20	79	891	5.67	<10	2.37	1107	117	0.01	9	2130	76	20	<20	29	0.05	<10	92	<10	1	306
28	G37158	1.3	2.69	40	45	<5	1.33	2	19	70	770	5.66	<10	2.63	1366	71	<0.01	8	2160	88	15	<20	34	0.05	<10	88	<10	1	293
29	G37159	1.1	2.69	40	50	<5	1.35	1	18	69	761	5.43	<10	2.63	1428	70	<0.01	6	2070	76	<5	<20	36	0.06	<10	88	<10	<1	287
30	G37160	1.3	2.83	35	60	<5	1.59	1	18	64	827	5.85	<10	2.78	1771	42	<0.01	6	2170	78	<5	<20	45	0.06	<10	104	<10	<1	305
31	G37161	1.9	2.73	25	40	<5	1.11	2	28	71	1306	6.86	<10	2.47	1310	54	<0.01	11	2300	112	15	<20	41	0.05	<10	96	<10	<1	311
32	G37162	1.2	2.12	15	40	<5	1.51	2	23	74	1020	5.43	<10	2.02	1348	60	0.01	8	2070	98	10	<20	48	0.05	<10	76	<10	<1	248
33	G37163	1.7	2.34	25	55	<5	1.06	3	31	76	1444	6.74	<10	1.98	1704	90	<0.01	14	1850	78	30	<20	52	0.04	<10	78	<10	<1	339
34	G37164	1.6	1.80	20	40	<5	0.92	3	22	92	1067	5.77	<10	1.63	1801	87	0.01	9	2030	122	15	<20	23	0.05	<10	62	<10	<1	373
35	G37165	1.7	2.58	20	45	<5	1.28	2	25	84	1045	7.04	<10	2.35	1260	73	<0.01	10	2140	124	15	<20	26	0.05	<10	107	<10	<1	446
QC DATA:																													
Repeat:																													
1	G37131	5.7	0.79	30	80	<5	1.40	3	10	127	1074	2.81	<10	0.38	723	20	<0.01	5	930	62	<5	<20	66	0.07	<10	16	<10	4	244
19	G37149	1.7	0.89	15	170	<5	2.35	<1	9	84	1163	3.48	<10	0.51	986	19	0.02	5	1050	30	<5	<20	131	0.09	<10	30	<10	6	114
Resplit:																													
1	G37131	6.0	0.69	10	70	<5	1.45	3	10	110	1001	2.77	<10	0.38	784	21	<0.01	5	940	66	5	<20	70	0.05	<10	14	<10	5	216
Standard:																													
Pb113		11.0	0.25	45	60	<5	1.64	35	2	6	2258	1.02	<10	0.09	1472	65	0.02	3	100	5510	15	<20	80	0.02	<10	7	<10	<1	6955

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5537S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5538

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

9-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07070
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35111	<0.03	<0.001
2	G35112	0.97	0.028
3	G35113	1.10	0.032
4	G35114	2.35	0.069
5	G35115	1.51	0.044
6	G35116	2.78	0.081
7	G35117	1.02	0.030
8	G35118	1.06	0.031
9	G35119	1.06	0.031
10	G35120	1.01	0.029
11	G35121	1.36	0.040
12	G35122	0.75	0.022
13	G35123	0.89	0.026
14	G35124	1.56	0.045
15	G35125	2.39	0.070
16	G35126	2.30	0.067
17	G35127	1.60	0.047
18	G35128	1.71	0.050
19	G35129	1.54	0.045
20	G35130	2.72	0.079
21	G35131	1.24	0.036
22	G35132	1.93	0.056
23	G35133	0.91	0.027
24	G35134	1.12	0.033
25	G35135	1.35	0.039
26	G35136	1.41	0.041
27	G35137	1.16	0.034
28	G35138	0.57	0.017

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5538 9-Oct-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G35139	1.33	0.039
30	G35140	1.24	0.036
31	G35141	1.63	0.048
32	G35142	1.07	0.031
33	G35143	0.72	0.021
34	G35144	0.30	0.009
35	G35145	0.31	0.009
QC DATA:			
Repeat:			
10	G35120	0.94	0.027
19	G35129	1.47	0.043
Resplits:			
2	G351112	0.87	0.025
Standard:			
SI25		1.79	0.052

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

2-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 2007- 5538

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07070
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35111	<0.2	0.95	15	255	10	0.61	<1	7	98	4	2.33	<10	0.56	552	3	0.11	7	950	22	<5	<20	77	0.16	<10	47	<10	5	52
2	G35112	2.7	0.21	60	45	<5	0.95	2	15	107	1352	8.56	<10	<0.01	401	13	0.01	9	770	30	<5	<20	77	0.05	<10	8	<10	<1	77
3	G35113	3.1	0.24	35	30	<5	2.02	<1	12	107	1749	4.51	<10	0.17	434	12	0.01	7	980	24	<5	<20	118	0.03	<10	11	<10	<1	25
4	G35114	4.4	0.26	15	35	<5	2.16	2	11	122	3204	4.32	<10	0.19	558	21	<0.01	7	930	46	<5	<20	136	0.02	<10	14	<10	<1	90
5	G35115	3.2	0.26	15	35	<5	2.13	2	11	126	2142	4.00	<10	0.18	659	13	<0.01	7	920	26	<5	<20	98	0.03	<10	13	<10	<1	70
6	G35116	4.2	0.25	<5	30	<5	1.41	3	14	156	3065	4.97	<10	0.09	576	20	<0.01	9	760	72	<5	<20	72	0.03	<10	10	<10	<1	110
7	G35117	2.5	0.27	10	25	<5	2.33	1	9	122	1877	3.39	<10	0.14	454	14	<0.01	7	1030	30	<5	<20	161	0.02	<10	12	<10	1	17
8	G35118	2.8	0.27	20	30	<5	2.02	1	8	153	2715	3.39	<10	0.20	537	16	0.01	8	800	22	<5	<20	119	0.01	<10	13	<10	<1	26
9	G35119	3.4	0.27	<5	35	<5	1.59	3	12	149	2798	4.83	<10	0.16	574	13	<0.01	8	720	48	<5	<20	80	0.03	<10	11	<10	<1	197
10	G35120	3.9	0.18	5	35	<5	1.42	2	13	137	3557	5.14	<10	0.12	417	13	<0.01	8	540	42	<5	<20	84	0.03	<10	10	<10	<1	39
11	G35121	2.6	0.26	20	35	<5	1.93	<1	9	130	2086	4.49	<10	0.13	543	13	<0.01	6	910	26	<5	<20	113	0.03	<10	12	<10	<1	22
12	G35122	4.3	0.22	<5	35	<5	1.39	1	13	172	2780	4.80	<10	0.01	521	13	<0.01	9	540	34	<5	<20	84	0.03	<10	10	<10	<1	20
13	G35123	4.2	0.28	10	30	<5	1.22	1	12	181	2505	4.53	<10	0.03	491	11	0.01	8	690	36	<5	<20	81	0.03	<10	12	<10	<1	32
14	G35124	10.2	0.23	160	35	<5	0.46	2	15	154	2719	5.44	<10	<0.01	188	14	<0.01	8	540	54	45	<20	29	0.03	<10	9	<10	<1	103
15	G35125	17.2	0.23	115	40	<5	0.73	4	12	158	2931	5.12	<10	0.16	752	12	<0.01	7	390	58	25	<20	37	0.03	<10	9	<10	<1	189
16	G35126	7.6	0.28	60	35	<5	0.25	4	13	188	3546	5.34	<10	<0.01	91	16	<0.01	8	660	182	<5	<20	22	0.03	<10	11	<10	<1	283
17	G35127	8.7	0.27	50	40	<5	0.56	4	20	187	2750	6.17	<10	<0.01	266	14	<0.01	10	630	214	10	<20	41	0.03	<10	10	<10	<1	257
18	G35128	5.3	0.35	30	35	<5	1.83	2	14	159	2704	5.47	<10	0.43	963	19	<0.01	10	1130	66	<5	<20	98	0.04	<10	12	<10	<1	39
19	G35129	3.1	0.58	15	35	<5	1.69	<1	10	98	2385	3.51	<10	0.47	882	14	<0.01	6	1150	32	<5	<20	89	0.03	<10	17	<10	2	62
20	G35130	4.3	0.68	25	35	<5	0.95	1	14	109	3570	4.78	<10	0.48	883	16	<0.01	7	840	50	<5	<20	49	0.03	<10	16	<10	<1	102
21	G35131	5.7	0.22	10	30	<5	0.62	4	17	153	4230	5.25	<10	0.05	414	12	<0.01	8	450	142	<5	<20	38	0.02	<10	11	<10	<1	185
22	G35132	8.3	0.26	30	35	<5	0.77	4	12	135	3580	5.42	<10	0.08	370	14	<0.01	8	620	90	10	<20	46	0.03	<10	11	<10	<1	218
23	G35133	26.5	0.22	210	30	<5	0.37	5	13	203	2849	4.49	<10	<0.01	216	14	<0.01	8	370	332	110	<20	39	0.02	<10	8	<10	<1	365
24	G35134	6.2	0.26	25	35	<5	1.43	2	13	167	3351	5.10	<10	0.13	719	16	0.01	7	690	60	<5	<20	162	0.03	<10	12	<10	<1	123
25	G35135	3.4	0.47	15	35	<5	1.47	<1	11	145	2629	4.68	<10	0.24	565	13	<0.01	7	820	38	<5	<20	117	0.03	<10	17	<10	<1	54

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35136	3.8	0.59	25	25	<5	0.58	<1	12	176	3098	4.57	<10	0.27	319	16	<0.01	8	770	30	<5	<20	26	0.02	<10	14	<10	<1	83
27	G35137	3.8	0.43	10	30	<5	0.79	2	12	154	3172	5.51	<10	0.11	337	15	<0.01	8	770	52	<5	<20	41	0.03	<10	14	<10	<1	80
28	G35138	3.3	0.31	<5	35	<5	1.12	2	12	137	2343	4.91	<10	0.05	390	16	<0.01	7	650	124	<5	<20	63	0.03	<10	10	<10	<1	120
29	G35139	3.2	0.38	20	30	<5	1.08	2	12	175	2218	5.03	<10	0.13	424	21	<0.01	9	620	52	<5	<20	265	0.02	<10	14	<10	<1	108
30	G35140	3.1	0.62	15	30	<5	1.47	1	14	124	1959	4.47	<10	0.30	574	17	<0.01	5	760	52	<5	<20	75	0.03	<10	13	<10	<1	79
31	G35141	7.1	0.47	40	30	<5	0.55	2	13	184	2452	5.43	<10	0.20	376	15	<0.01	8	540	68	<5	<20	33	0.03	<10	11	<10	<1	95
32	G35142	4.1	0.27	20	30	<5	0.28	2	11	187	2444	4.95	<10	0.01	167	15	<0.01	8	560	102	<5	<20	24	0.02	<10	13	<10	<1	98
33	G35143	5.4	0.24	20	35	<5	0.12	3	12	188	2111	5.86	<10	<0.01	39	15	<0.01	9	400	92	<5	<20	15	0.03	<10	14	<10	<1	142
34	G35144	19.9	0.16	110	30	<5	0.08	6	15	170	2128	5.28	<10	<0.01	31	15	<0.01	7	250	40	115	<20	15	0.03	<10	12	<10	<1	409
35	G35145	3.2	1.09	35	45	<5	0.96	2	21	59	2609	3.43	10	0.56	185	188	0.03	13	500	60	20	<20	48	0.05	<10	44	<10	7	261
QC DATA:																													
Repeat:																													
2	G35112	2.8	0.22	50	40	<5	1.01	3	15	107	1357	8.43	<10	0.01	396	14	0.01	9	760	30	5	<20	82	0.04	<10	8	<10	<1	77
10	G35120	3.9	0.19	<5	35	<5	1.45	3	13	142	3616	5.29	<10	0.13	427	17	0.01	10	520	44	5	<20	86	0.01	<10	11	<10	<1	40
19	G35129	3.1	0.61	20	35	<5	1.72	<1	10	101	2408	3.61	<10	0.48	894	14	<0.01	6	1140	32	<5	<20	92	0.03	<10	18	<10	2	65
Resplit:																													
2	G35112	2.7	0.21	75	45	<5	0.80	1	15	106	1292	9.00	<10	<0.01	374	12	0.01	5	780	30	<5	<20	68	0.06	<10	7	<10	<1	78
Standard:																													
Pb113		11.6	0.26	40	55	<5	1.67	37	2	5	2229	1.10	<10	0.10	1478	67	0.02	3	90	5574	20	<20	88	0.02	<10	8	<10	<1	7010

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5537
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5539

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07071
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	G35146	0.39	0.011	69.3	2.021
2	G35147	1.05	0.031	227	6.620
3	G35148	0.45	0.013	100	2.916
4	G35149	0.86	0.025		
5	G35150	0.83	0.024		
6	G35151	0.53	0.015		
7	G35152	0.43	0.013		
8	G35153	<0.03	<0.001		
9	G35154	0.81	0.024		
10	G35155	1.48	0.043		
11	G35156	0.63	0.018		
12	G35157	0.48	0.014		
13	G35158	0.54	0.016		
14	G35159	0.97	0.028		
15	G35160	1.08	0.031		
16	G35161	0.56	0.016		
17	G35162	0.53	0.015		
18	G35163	0.25	0.007		
19	G35164	0.15	0.004		
20	G35165	0.34	0.010		
21	G35166	0.92	0.027		
22	G35167	0.53	0.015		
23	G35168	0.32	0.009		
24	G35169	0.26	0.008		
25	G35170	0.69	0.020		
26	G35171	0.31	0.009		
27	G35172	0.35	0.010		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5539 17-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
28	G35173	0.57	0.017		
29	G35174	<0.03	<0.001		
30	G35175	0.54	0.016		
31	G35176	0.81	0.024		
32	G35177	1.22	0.036		
33	G35178	0.92	0.027		
34	G35179	1.00	0.029		
35	G35180	0.85	0.025		
QC DATA:					
Repeat:					
1	G35146	0.39	0.011	69.3	2.021
2	G35147	1.06	0.031		
5	G35150	0.78	0.023		
10	G35155	1.41	0.041		
19	G35164	0.16	0.005		
32	G35177	1.26	0.037		
Resplits:					
1	G35146	0.46	0.013		
Standard:					
SI25		1.81	0.053		
Pb113				22.6	0.659

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

20-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5539

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07071
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35146	>30	0.18	80	40	<5	0.06	11	15	213	2134	4.62	<10	<0.01	41	18	<0.01	10	70	450	160	<20	19	0.01	<10	10	<10	<1	361
2	G35147	>30	0.22	200	45	<5	0.28	43	8	171	3821	2.98	<10	0.11	284	16	<0.01	10	30	1478	405	<20	43	<0.01	<10	7	<10	<1	1893
3	G35148	>30	0.24	125	45	<5	0.75	26	10	207	3362	4.04	<10	0.20	708	17	<0.01	6	130	620	435	<20	45	0.02	<10	12	<10	<1	1503
4	G35149	3.2	0.94	<5	50	<5	0.89	7	13	125	2362	5.13	<10	0.64	655	14	0.01	7	630	100	10	<20	71	0.02	<10	23	<10	<1	182
5	G35150	3.9	0.47	<5	40	<5	0.56	5	12	173	3323	6.40	<10	0.21	437	14	0.02	8	350	74	<5	<20	44	0.02	<10	25	<10	<1	138
6	G35151	4.4	0.27	<5	55	<5	0.41	5	15	191	3430	5.99	<10	<0.01	197	13	0.01	8	190	66	<5	<20	59	0.02	<10	18	<10	<1	102
7	G35152	3.6	0.24	<5	50	<5	0.80	3	12	200	3203	4.89	<10	<0.01	210	18	0.01	10	230	52	<5	<20	73	0.03	<10	16	<10	<1	47
8	G35153	<0.2	1.01	<5	240	30	0.62	<1	7	123	11	2.26	<10	0.56	549	1	0.11	4	780	22	<5	<20	87	0.11	<10	46	<10	2	42
9	G35154	3.6	0.35	<5	60	<5	1.11	10	18	188	2893	6.42	<10	0.12	586	38	0.01	7	250	274	<5	<20	66	0.02	<10	19	<10	<1	486
10	G35155	4.5	0.37	<5	55	<5	1.28	7	11	180	3575	5.61	<10	0.13	409	17	0.01	7	250	106	<5	<20	95	0.02	<10	20	<10	<1	320
11	G35156	5.7	0.29	<5	50	<5	0.71	6	16	189	3391	6.56	<10	<0.01	207	16	0.01	12	310	112	10	<20	48	<0.01	<10	17	<10	<1	158
12	G35157	5.2	0.29	<5	60	<5	0.33	3	12	227	2771	6.50	<10	<0.01	204	26	0.01	9	220	50	<5	<20	28	0.02	<10	23	<10	<1	50
13	G35158	3.3	0.26	<5	55	<5	0.34	15	11	223	2757	5.94	<10	<0.01	169	22	0.01	9	180	148	<5	<20	36	0.02	<10	22	<10	<1	740
14	G35159	3.5	0.27	<5	55	<5	0.95	15	12	225	3044	5.90	<10	<0.01	267	19	0.01	8	250	102	<5	<20	70	0.02	<10	21	<10	<1	898
15	G35160	3.6	0.37	<5	60	<5	0.90	6	13	164	3854	7.74	<10	0.10	308	14	0.01	9	120	36	<5	<20	59	0.02	<10	41	<10	<1	241
16	G35161	2.6	0.26	<5	55	<5	0.44	3	11	219	2426	5.29	<10	<0.01	220	16	0.01	8	240	40	<5	<20	36	0.02	<10	32	<10	<1	82
17	G35162	2.7	0.27	<5	50	<5	0.42	3	9	219	2713	5.18	<10	<0.01	209	10	0.01	9	240	38	<5	<20	37	0.02	<10	32	<10	<1	66
18	G35163	2.9	0.21	<5	45	<5	0.31	2	14	230	3309	5.17	<10	<0.01	130	17	0.01	8	40	26	<5	<20	33	0.01	<10	28	<10	<1	27
19	G35164	3.6	0.14	<5	40	<5	0.33	2	16	170	2492	5.28	<10	<0.01	77	15	<0.01	5	30	24	10	<20	37	0.02	<10	15	<10	<1	24
20	G35165	4.3	0.17	5	50	<5	0.26	4	16	209	3809	7.38	<10	<0.01	123	16	<0.01	10	<10	34	30	<20	29	0.02	<10	14	<10	<1	65
21	G35166	3.3	0.34	<5	50	<5	0.82	6	10	166	2822	5.82	<10	0.08	346	14	0.01	7	220	68	<5	<20	50	0.02	<10	18	<10	<1	205
22	G35167	4.5	0.18	<5	40	<5	0.35	5	12	187	3990	5.76	<10	<0.01	52	16	0.01	10	90	50	5	<20	39	<0.01	<10	17	<10	<1	75
23	G35168	7.3	0.14	50	45	<5	0.33	3	12	225	3739	4.87	<10	<0.01	37	8	0.01	8	<10	20	80	<20	41	0.01	<10	17	<10	<1	41
24	G35169	4.8	0.16	<5	35	<5	0.47	3	11	208	3356	4.74	<10	<0.01	118	19	0.01	7	20	24	30	<20	40	0.01	<10	17	<10	<1	39
25	G35170	4.3	0.23	<5	40	<5	0.77	4	14	217	4754	5.17	<10	<0.01	226	22	0.01	6	20	42	<5	<20	54	<0.01	<10	27	<10	<1	131

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35171	3.5	0.18	<5	45	<5	1.04	4	10	227	2300	4.61	<10	<0.01	224	17	0.01	6	70	56	<5	<20	94	0.02	<10	26	<10	<1	118
27	G35172	3.2	0.19	<5	45	<5	0.42	5	20	259	2499	5.71	<10	<0.01	87	21	0.01	10	100	64	<5	<20	48	0.02	<10	23	<10	<1	147
28	G35173	2.7	0.51	<5	90	<5	0.27	5	12	208	2585	5.63	<10	0.25	268	24	<0.01	11	160	40	5	<20	57	0.03	<10	30	<10	<1	111
29	G35174	<0.2	1.08	<5	250	15	0.66	<1	7	102	10	2.19	<10	0.56	544	2	0.13	4	770	24	<5	<20	98	0.11	<10	46	<10	3	41
30	G35175	4.5	0.25	<5	55	<5	0.49	5	12	221	2932	5.45	<10	0.01	165	14	0.01	6	110	64	<5	<20	60	0.02	<10	30	<10	<1	129
31	G35176	5.5	0.21	<5	40	<5	0.72	6	11	224	3490	4.99	<10	0.04	191	19	0.01	8	30	70	10	<20	62	0.01	<10	20	<10	<1	234
32	G35177	2.7	0.49	<5	40	<5	1.36	3	10	162	2165	5.29	<10	0.20	426	14	0.01	6	310	42	<5	<20	90	0.02	<10	22	<10	<1	88
33	G35178	3.0	0.49	<5	45	<5	1.08	5	10	163	2377	5.64	<10	0.25	469	19	0.01	9	280	52	10	<20	76	0.01	<10	26	<10	<1	122
34	G35179	4.1	0.35	<5	45	<5	0.37	7	14	170	2552	5.61	<10	0.14	273	20	0.01	8	270	102	<5	<20	33	0.02	<10	21	<10	<1	277
35	G35180	4.0	0.53	<5	50	<5	0.43	3	12	227	2626	5.34	<10	0.33	494	17	0.01	8	150	58	5	<20	33	0.02	<10	26	<10	<1	91
QC DATA:																													
Repeat:																													
1	G35146	>30	0.18	90	40	<5	0.06	10	15	211	2080	4.52	<10	<0.01	41	19	<0.01	8	80	446	150	<20	19	0.02	<10	10	<10	<1	357
10	G35155	4.4	0.37	<5	55	<5	1.26	7	11	180	3533	5.50	<10	0.13	406	17	0.01	7	250	104	<5	<20	91	0.01	<10	21	<10	<1	318
19	G35164	3.6	0.14	<5	35	<5	0.33	3	16	172	2482	5.28	<10	<0.01	77	14	0.01	7	20	22	15	<20	35	0.02	<10	15	<10	<1	24
Resplit:																													
1	G35146	>30	0.21	90	30	<5	0.07	14	13	234	2221	4.39	<10	<0.01	47	17	0.01	10	90	460	170	<20	18	0.01	<10	12	<10	<1	366
Standard:																													
Pb113		11.0	0.27	40	55	<5	1.61	40	2	6	2281	1.01	<10	0.09	1473	68	0.02	3	70	5350	25	<20	81	<0.01	<10	7	<10	<1	6917

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5539s
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5540

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07072
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37166	0.58	0.017
2	G37167	0.62	0.018
3	G37168	0.46	0.013
4	G37169	0.40	0.012
5	G37170	0.99	0.029
6	G37171	1.07	0.031
7	G37172	0.77	0.022
8	G37173	0.60	0.017
9	G37174	0.57	0.017
10	G37175	0.58	0.017
11	G37176	1.17	0.034
12	G37177	0.97	0.028
13	G37178	0.86	0.025
14	G37179	0.68	0.020
15	G37180	0.76	0.022
16	G37181	1.08	0.031
17	G37182	0.70	0.020
18	G37183	1.36	0.040
19	G37184	<0.03	<0.001
20	G37185	0.86	0.025
21	G37186	0.53	0.015
22	G37187	1.13	0.033
23	G37188	0.75	0.022
24	G37189	0.56	0.016
25	G37190	0.62	0.018
26	G37191	0.90	0.026
27	G37192	0.47	0.014

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5540 17-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G37193	1.30	0.038
29	G37194	0.45	0.013
30	G37195	0.57	0.017
31	G37196	1.20	0.035
32	G37197	1.14	0.033
33	G37198	0.63	0.018
34	G37199	0.87	0.025
35	G37200	0.85	0.025
QC DATA:			
Repeat:			
1	G37166	0.62	0.018
6	G37171	1.19	0.035
10	G37175	0.69	0.020
11	G37176	1.13	0.033
16	G37181	1.12	0.033
18	G37183	1.40	0.041
22	G37187	1.15	0.034
28	G37193	1.23	0.036
31	G37196	1.25	0.036
32	G37197	1.21	0.035
Resplits:			
1	G37166	0.64	0.019
Standard:			
SI25		1.81	0.053

AU: 30g FA/AA-Finish

JJ/jl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

2-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5540

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07072
Submitted by: Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37166	1.3	2.64	35	40	<5	0.83	1	26	106	830	7.16	<10	2.34	1480	65	0.01	14	2240	106	15	<20	19	0.06	<10	99	<10	<1	419
2	G37167	1.6	2.08	25	35	<5	0.70	2	24	98	999	6.41	<10	1.78	1489	87	0.01	9	1920	116	5	<20	20	0.05	<10	70	<10	<1	318
3	G37168	0.9	2.65	15	65	<5	1.01	2	18	74	681	6.69	<10	2.47	2032	62	0.01	8	2440	114	5	<20	22	0.06	<10	100	<10	<1	406
4	G37169	0.8	2.64	45	45	<5	0.71	2	21	80	753	6.83	<10	2.27	1782	92	0.01	13	2320	102	25	<20	24	0.05	<10	91	<10	<1	415
5	G37170	3.7	1.03	65	50	<5	0.72	3	17	57	3209	3.86	20	0.46	267	214	0.03	14	410	134	30	<20	28	0.04	<10	41	<10	5	169
6	G37171	1.7	1.92	20	35	<5	0.55	3	28	108	1228	6.52	<10	1.58	1250	95	0.01	8	1730	140	<5	<20	23	0.05	<10	60	<10	<1	331
7	G37172	1.3	2.49	20	40	<5	0.54	3	29	124	997	7.42	<10	2.09	2012	66	0.01	11	2000	124	5	<20	25	0.07	<10	87	<10	<1	475
8	G37173	4.4	1.88	10	40	<5	0.55	4	24	85	1204	7.93	<10	1.56	1431	42	0.01	10	1990	186	<5	<20	22	0.06	<10	68	<10	<1	372
9	G37174	1.6	1.79	35	40	<5	0.74	3	25	93	891	7.25	<10	1.81	1654	49	0.01	8	1750	254	<5	<20	20	0.06	<10	66	<10	<1	355
10	G37175	1.2	1.27	<5	40	<5	0.64	1	22	99	887	6.29	<10	1.56	1584	41	0.01	7	2070	96	<5	<20	15	0.05	<10	49	<10	<1	356
11	G37176	2.4	0.75	20	40	<5	0.67	10	24	118	1164	7.33	<10	1.10	1502	76	0.02	11	1700	174	5	<20	19	0.06	<10	30	<10	<1	428
12	G37177	2.7	0.60	<5	40	<5	0.68	2	23	115	1230	5.93	<10	1.12	1633	124	0.02	4	2070	154	<5	<20	24	0.07	<10	36	<10	2	308
13	G37178	2.2	1.03	25	50	<5	0.63	2	21	95	1068	6.19	<10	1.50	1473	58	0.02	9	1850	106	<5	<20	18	0.05	<10	41	<10	<1	373
14	G37179	2.3	1.04	10	40	<5	0.48	2	22	119	1328	6.25	<10	1.14	1185	74	0.02	10	1710	44	<5	<20	26	0.05	<10	39	<10	<1	319
15	G37180	1.7	1.05	15	40	<5	0.46	2	20	95	990	6.74	<10	1.21	1572	71	0.02	10	2060	78	10	<20	43	0.05	<10	39	<10	<1	327
16	G37181	2.4	1.63	25	40	<5	0.46	2	26	100	1430	7.31	<10	1.68	1620	76	0.02	10	2090	84	<5	<20	32	0.06	<10	62	<10	<1	518
17	G37182	4.2	1.06	<5	40	<5	0.45	27	26	108	1128	7.29	<10	1.13	1448	72	0.02	10	1980	184	<5	<20	27	0.06	<10	42	<10	<1	1081
18	G37183	2.8	0.84	20	40	<5	0.35	3	29	110	1563	7.29	<10	1.20	1709	82	0.02	10	1160	122	5	<20	35	0.06	<10	23	<10	<1	252
19	G37184	<0.2	0.96	10	250	15	0.61	<1	7	98	6	2.19	<10	0.54	530	4	0.12	10	910	20	10	<20	84	0.13	<10	44	<10	5	50
20	G37185	1.4	1.24	<5	45	<5	0.46	2	17	101	946	5.59	<10	1.39	1633	99	0.02	8	1940	66	<5	<20	25	0.05	<10	51	<10	<1	391
21	G37186	1.4	1.61	30	45	<5	0.49	2	18	105	671	7.22	<10	1.83	2698	58	0.02	10	2080	200	<5	<20	28	0.07	<10	72	<10	<1	526
22	G37187	3.0	1.14	<5	40	<5	0.39	3	24	109	1322	7.80	<10	1.43	2710	71	0.02	10	1580	280	<5	<20	19	0.07	<10	46	<10	<1	425
23	G37188	2.3	1.28	10	40	<5	0.47	3	21	109	821	6.87	<10	1.80	2787	56	0.02	12	2020	264	5	<20	25	0.07	<10	54	<10	<1	515
24	G37189	0.9	0.99	<5	45	<5	0.52	2	20	96	764	7.06	<10	2.27	4418	77	0.02	9	2110	78	10	<20	23	0.09	<10	52	<10	<1	508
25	G37190	1.3	0.98	<5	45	<5	0.52	2	24	84	1013	7.51	<10	2.20	4393	54	0.02	9	2120	84	<5	<20	28	0.09	<10	51	<10	<1	519

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37191	1.5	1.21	10	45	<5	0.51	9	20	106	1066	6.99	<10	2.60	4328	84	0.02	19	2010	110	45	<20	20	0.06	<10	59	<10	<1	849
27	G37192	2.9	0.86	10	35	<5	0.56	9	20	110	889	6.24	<10	1.22	1652	52	0.02	9	1940	276	<5	<20	27	0.05	<10	37	<10	<1	965
28	G37193	1.5	0.71	<5	40	<5	0.50	7	19	97	1237	6.71	<10	1.63	2754	66	0.02	12	1890	104	25	<20	22	0.05	<10	37	<10	<1	624
29	G37194	2.9	0.53	<5	35	<5	0.63	5	15	128	1215	5.62	<10	0.91	1548	48	0.02	5	2300	208	<5	<20	20	0.05	<10	28	<10	<1	507
30	G37195	4.3	0.71	10	40	<5	0.55	6	19	104	1425	6.91	<10	1.26	1977	37	0.02	8	1930	194	5	<20	20	0.05	<10	28	<10	<1	577
31	G37196	2.0	0.81	10	45	<5	0.67	4	22	109	1374	7.19	<10	1.69	2246	51	0.02	8	1770	76	<5	<20	22	0.07	<10	35	<10	<1	479
32	G37197	2.2	1.08	10	35	<5	0.68	3	23	105	1615	5.77	<10	1.76	1618	49	0.01	6	1600	150	<5	<20	25	0.05	<10	38	<10	<1	456
33	G37198	1.5	1.96	15	45	<5	0.61	2	18	80	869	6.26	<10	2.61	1883	62	0.02	8	1770	96	10	<20	29	0.06	<10	70	<10	<1	398
34	G37199	2.0	1.75	25	35	<5	0.64	1	26	85	1593	6.52	<10	2.18	1630	57	0.02	7	1830	106	10	<20	18	0.06	<10	64	<10	<1	328
35	G37200	2.5	1.13	<5	35	<5	0.78	2	25	93	1530	6.35	<10	1.64	2042	41	0.01	6	1460	148	<5	<20	26	0.06	<10	43	<10	<1	335
QC DATA:																													
Repeat:																													
1	G37166	1.4	2.72	35	45	5	0.84	2	28	111	858	7.30	<10	2.41	1514	76	0.01	17	2350	124	25	<20	26	0.06	<10	102	<10	2	425
10	G37175	1.2	1.34	<5	45	<5	0.66	3	23	103	919	6.45	<10	1.63	1632	48	0.01	14	2180	106	5	<20	18	0.05	<10	52	<10	<1	361
20	G37185	1.5	1.35	5	35	<5	0.49	2	18	111	999	5.94	<10	1.51	1740	94	0.02	8	2060	74	5	<20	23	0.05	<10	55	<10	<1	411
Resplit:																													
1	G37166	1.5	2.65	40	40	<5	0.79	1	26	98	842	7.38	<10	2.40	1545	89	0.01	12	2200	102	20	<20	24	0.06	<10	98	<10	<1	425
Standard:																													
Pb113		11.2	0.25	65	50	<5	1.68	38	2	5	2264	1.05	<10	0.13	1395	73	0.02	10	90	5534	15	<20	90	<0.01	<10	11	<10	<1	7076

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
dl/5537
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5541

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

12-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07073
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37201	0.87	0.025
2	G37202	0.68	0.020
3	G37203	0.54	0.016
4	G37204	0.89	0.026
5	G37205	0.67	0.020
6	G37206	0.77	0.022
7	G37207	0.64	0.019
8	G37208	0.70	0.020
9	G37209	<0.03	<0.001
10	G37210	0.79	0.023
11	G37211	0.39	0.011
12	G37212	0.86	0.025
13	G37213	0.61	0.018
14	G37214	0.46	0.013
15	G37215	0.63	0.018
16	G37216	0.89	0.026
17	G37217	0.56	0.016
18	G37218	1.04	0.030
19	G37219	0.80	0.023
20	G37220	1.04	0.030
21	G37221	0.55	0.016
22	G37222	0.27	0.008
23	G37223	0.57	0.017
24	G37224	0.60	0.017
25	G37225	0.77	0.022
26	G37226	0.58	0.017
27	G37227	0.91	0.027

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7 - 5541

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G37228	1.16	0.034
29	G37229	0.84	0.024
30	G37230	0.63	0.018
31	G37231	0.44	0.013
32	G37232	0.59	0.017
33	G37233	1.35	0.039
34	G37234	0.99	0.029
35	G37235	1.26	0.037

QC DATA:

Repeat:

1	G37201	0.83	0.024
10	G37210	0.83	0.024
18	G37218	1.00	0.029
19	G37219	0.79	0.023
20	G37220	1.09	0.032
28	G37228	1.12	0.033
33	G37233	1.47	0.043
35	G37235	1.15	0.034

Resplits:

1	G37201	0.80	0.023

Standard:

OXI54		1.82	0.053

AU: 30g FA/AA-Finish

JJ/jl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

18-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5541

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07073
Submitted by: Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37201	1.9	1.04	20	40	<5	0.66	2	16	65	1235	5.59	<10	1.66	2401	63	0.02	2	2140	48	<5	<20	24	<0.01	<10	31	<10	4	252
2	G37202	2.2	1.01	25	40	<5	1.32	3	18	70	1092	6.49	<10	1.94	2692	53	0.02	2	2380	112	<5	<20	30	<0.01	<10	31	<10	5	252
3	G37203	1.6	0.87	20	40	<5	1.03	2	15	105	989	6.48	<10	1.66	2272	69	0.02	2	2240	62	<5	<20	26	<0.01	<10	30	<10	4	211
4	G37204	2.4	0.88	20	40	<5	0.93	4	18	74	1527	5.84	<10	1.42	1709	59	0.02	2	2060	84	<5	<20	28	<0.01	<10	27	<10	4	275
5	G37205	1.9	1.12	25	40	<5	0.75	2	18	98	1182	6.37	<10	1.92	2262	36	0.02	2	2260	46	<5	<20	28	<0.01	<10	31	<10	4	244
6	G37206	1.8	0.71	20	35	<5	1.03	4	16	111	1278	5.32	<10	1.23	1570	90	0.01	2	1180	70	<5	<20	36	<0.01	<10	13	<10	2	164
7	G37207	2.3	0.79	30	40	<5	1.02	5	14	104	1103	4.99	<10	1.14	1483	47	0.02	2	1700	172	5	<20	29	<0.01	<10	16	<10	3	170
8	G37208	1.8	1.28	40	45	5	0.60	6	20	100	1535	9.38	<10	1.85	2470	101	0.02	2	2630	106	<5	<20	23	<0.01	<10	27	<10	3	300
9	G37209	<0.2	1.21	10	255	<5	0.68	<1	7	106	4	2.26	<10	0.63	586	2	0.10	8	990	8	<5	<20	83	0.14	<10	43	<10	5	45
10	G37210	1.5	1.14	60	40	<5	0.57	2	20	99	1228	7.61	<10	1.73	2698	63	0.02	2	2700	44	<5	<20	21	<0.01	<10	28	<10	4	219
11	G37211	1.2	0.91	30	40	5	0.50	2	14	116	779	6.42	<10	1.41	1842	49	0.02	3	2100	54	<5	<20	17	<0.01	<10	29	<10	3	197
12	G37212	1.4	0.71	15	55	<5	0.66	3	13	112	992	6.41	<10	1.82	2188	118	0.02	4	1650	64	<5	<20	21	<0.01	<10	21	<10	3	285
13	G37213	1.5	0.67	15	55	<5	0.96	2	15	102	950	6.45	<10	2.27	2095	80	0.01	4	1810	48	<5	<20	26	<0.01	<10	32	<10	4	239
14	G37214	0.8	0.68	15	55	10	0.63	3	12	106	526	6.23	<10	2.15	2177	39	0.02	3	1850	28	<5	<20	22	<0.01	<10	34	<10	4	364
15	G37215	1.5	0.74	15	40	<5	1.07	2	14	102	1200	4.80	<10	1.18	994	108	0.01	3	1580	60	<5	<20	49	<0.01	<10	18	<10	3	177
16	G37216	1.8	0.68	15	45	<5	2.00	4	17	78	1465	5.81	<10	1.46	1022	51	0.02	3	1640	198	<5	<20	63	<0.01	<10	24	<10	3	257
17	G37217	1.4	0.58	10	55	<5	0.91	3	16	106	981	5.99	<10	1.41	1360	45	0.01	4	2110	32	<5	<20	59	<0.01	<10	23	<10	3	318
18	G37218	2.1	0.61	10	65	<5	0.81	2	16	92	1512	5.14	<10	1.44	1187	43	0.01	4	1640	30	<5	<20	52	<0.01	<10	17	<10	3	219
19	G37219	1.8	0.57	10	35	<5	0.94	2	12	133	1406	4.08	<10	0.88	638	102	0.01	4	1550	40	<5	<20	44	<0.01	<10	14	<10	2	169
20	G37220	1.9	0.76	10	45	<5	1.55	3	15	108	1619	5.45	<10	1.64	1030	118	0.01	4	1550	56	<5	<20	69	<0.01	<10	18	<10	3	255
21	G37221	1.0	0.48	5	65	<5	1.77	1	9	104	751	3.79	<10	1.38	856	54	0.01	4	1320	22	<5	<20	153	<0.01	<10	14	<10	3	137
22	G37222	3.0	1.21	35	55	<5	0.94	2	18	54	2618	3.37	20	0.61	200	186	0.03	12	630	50	5	<20	61	0.04	<10	38	<10	8	263
23	G37223	0.9	0.44	5	45	<5	2.85	1	8	129	803	3.35	<10	1.15	687	51	0.01	5	1230	26	<5	<20	291	<0.01	<10	12	<10	2	91
24	G37224	0.9	0.62	5	45	<5	2.63	2	10	121	773	3.68	<10	1.18	789	42	0.01	5	1380	22	<5	<20	274	<0.01	<10	13	<10	2	184
25	G37225	1.2	0.56	10	50	<5	1.10	1	10	118	894	4.08	<10	1.13	765	82	0.01	5	1500	28	<5	<20	129	<0.01	<10	14	<10	2	142

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37226	1.1	1.04	20	60	<5	2.52	2	10	83	836	4.04	<10	1.73	1051	40	0.02	4	1400	22	<5	<20	240	<0.01	<10	22	<10	3	285
27	G37227	1.4	1.17	10	50	<5	3.17	2	10	98	919	3.72	<10	2.01	1070	72	0.02	7	1050	30	<5	<20	267	<0.01	<10	31	<10	3	337
28	G37228	2.2	1.20	10	45	<5	2.92	2	13	93	1291	4.45	<10	2.07	1196	47	0.02	7	960	30	<5	<20	266	<0.01	<10	29	<10	3	323
29	G37229	2.2	1.05	10	40	<5	3.50	1	13	120	1336	3.89	<10	1.82	1000	66	0.02	5	1180	34	<5	<20	337	<0.01	<10	25	<10	3	215
30	G37230	1.5	0.78	10	45	<5	3.28	2	9	98	858	3.61	<10	1.53	1176	41	0.01	5	1310	32	<5	<20	273	<0.01	<10	15	<10	2	212
31	G37231	1.2	0.42	10	55	<5	2.74	2	8	122	571	3.73	<10	1.54	1163	70	0.01	4	1330	32	<5	<20	190	<0.01	<10	13	<10	3	184
32	G37232	1.4	0.51	15	50	<5	1.97	3	11	129	861	3.92	<10	1.33	1037	49	0.01	6	1510	50	<5	<20	31	<0.01	<10	17	<10	3	281
33	G37233	1.8	0.52	10	30	<5	1.20	1	11	121	1387	3.74	<10	0.68	625	59	0.01	5	1290	20	<5	<20	101	<0.01	<10	11	<10	2	126
34	G37234	2.5	0.60	20	30	<5	1.04	2	12	155	1631	3.87	<10	0.74	675	48	0.01	6	1250	40	<5	<20	63	<0.01	<10	12	<10	2	160
35	G37235	2.2	0.72	15	30	<5	0.92	1	15	114	1436	3.92	<10	0.96	884	95	0.01	5	1390	24	<5	<20	38	<0.01	<10	11	<10	2	177
QC DATA:																													
Repeat:																													
1	G37201	2.0	1.14	20	55	<5	0.66	2	16	67	1250	5.56	<10	1.66	2387	56	0.02	1	2150	48	<5	<20	24	<0.01	<10	34	<10	4	251
10	G37210	1.7	1.18	60	40	<5	0.56	2	20	103	1251	7.76	<10	1.75	2750	66	0.02	2	2770	42	<5	<20	22	<0.01	<10	31	<10	4	225
19	G37219	1.7	0.57	10	35	<5	0.92	2	12	134	1380	3.93	<10	0.84	637	101	0.01	5	1510	40	<5	<20	43	<0.01	<10	14	<10	2	170
Resplit:																													
1	G37201	2.1	1.04	15	35	<5	0.66	2	16	90	1231	5.62	<10	1.53	2333	67	0.02	2	2230	52	<5	<20	23	<0.01	<10	32	<10	4	249
Standard:																													
Pb113		11.5	0.25	40	50	<5	1.67	40	2	5	2296	1.03	<10	0.11	1429	61	0.02	2	<10	5538	15	<20	89	0.02	<10	7	10	<1	6964

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/n5541S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5542

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

18-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07074
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37236	0.84	0.024
2	G37237	1.50	0.044
3	G37238	0.84	0.024
4	G37239	0.65	0.019
5	G37240	0.86	0.025
6	G37241	0.80	0.023
7	G37242	0.74	0.022
8	G37243	0.90	0.026
9	G37244	1.29	0.038
10	G37245	0.76	0.022
11	G37246	0.62	0.018
12	G37247	<0.03	<0.001
13	G37248	1.08	0.031
14	G37249	0.96	0.028
15	G37250	0.72	0.021
16	G37251	0.96	0.028
17	G37252	1.28	0.037
18	G37253	1.00	0.029
19	G37254	1.02	0.030
20	G37255	1.11	0.032
21	G37256	0.81	0.024
22	G37257	0.84	0.024
23	G37258	1.21	0.035
24	G37259	1.34	0.039
25	G37260	0.81	0.024
26	G37261	1.04	0.030
27	G37262	1.16	0.034

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 5542 18-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G37263	0.98	0.029
29	G37264	1.03	0.030
30	G37265	0.98	0.029
31	G37266	0.96	0.028
32	G37267	0.90	0.026
33	G37268	0.86	0.025
34	G37269	0.76	0.022
35	G37270	1.09	0.032

QC DATA:

Repeat:

1	G37236	0.82	0.024
2	G37237	1.38	0.040
9	G37244	1.25	0.036
10	G37245	0.76	0.022
19	G37254	1.01	0.029
24	G37259	1.19	0.035

Resplits:

1	G37236	0.76	0.022

Standard:

SI25		1.82	0.053

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

18-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5542

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07074
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37236	1.1	0.83	15	65	<5	0.84	1	13	108	908	4.40	<10	1.56	1554	74	0.01	7	1290	30	10	<20	48	0.03	<10	22	<10	<1	169
2	G37237	2.3	0.88	15	45	<5	0.60	<1	13	112	1241	3.86	<10	0.95	632	54	0.01	8	1380	36	10	<20	25	0.02	<10	23	<10	<1	155
3	G37238	1.7	0.93	10	55	<5	1.91	2	14	135	1213	4.26	<10	1.64	1342	94	0.01	9	960	50	10	<20	141	0.02	<10	28	<10	<1	193
4	G37239	1.1	1.18	15	70	<5	2.68	2	11	76	699	3.71	<10	1.75	1135	47	0.01	7	1360	78	15	<20	150	0.02	<10	32	<10	<1	191
5	G37240	1.8	1.44	20	55	<5	2.04	1	13	104	1285	4.02	<10	1.80	945	43	0.01	8	1390	42	15	<20	189	0.02	<10	35	<10	<1	210
6	G37241	1.3	1.37	20	45	<5	3.25	<1	11	120	1110	4.11	<10	1.84	963	80	0.01	8	1190	50	15	<20	303	0.02	<10	34	<10	<1	147
7	G37242	1.2	1.36	10	40	<5	3.84	2	11	125	1014	4.01	<10	1.90	1002	47	0.01	8	1090	40	15	<20	349	0.02	<10	34	<10	<1	145
8	G37243	1.6	0.86	10	40	<5	1.33	2	16	121	1359	4.57	<10	0.90	660	54	0.01	11	1190	58	10	<20	109	0.02	<10	21	<10	<1	118
9	G37244	1.8	0.75	15	40	<5	0.62	<1	16	133	1702	4.23	<10	0.73	656	107	0.01	8	1070	28	<5	<20	40	0.02	<10	16	<10	<1	132
10	G37245	1.8	0.41	15	30	<5	0.49	1	15	136	1351	4.61	<10	0.26	279	56	0.01	10	1020	36	<5	<20	36	0.01	<10	10	<10	<1	77
11	G37246	2.0	0.52	10	35	<5	0.80	1	14	120	1384	4.47	<10	0.46	442	65	0.01	9	1010	68	<5	<20	69	0.02	<10	11	<10	<1	85
12	G37247	<0.2	0.99	15	250	10	0.62	<1	6	135	7	2.22	<10	0.57	550	2	0.12	7	920	18	10	<20	80	0.12	<10	45	<10	3	45
13	G37248	1.3	1.01	15	45	<5	1.10	1	14	114	1463	3.83	<10	1.01	587	79	0.01	8	1240	46	5	<20	50	0.02	<10	22	<10	<1	149
14	G37249	1.8	1.49	30	45	<5	1.34	1	14	124	1374	4.49	<10	1.50	864	114	0.01	9	1180	48	10	<20	66	0.02	<10	31	<10	<1	270
15	G37250	1.4	1.75	30	70	<5	1.91	1	11	87	1194	3.91	<10	1.93	1101	41	0.01	6	1150	36	15	<20	433	0.02	<10	35	<10	<1	270
16	G37251	2.3	0.46	15	35	<5	1.02	2	16	129	1188	4.85	<10	0.46	594	156	0.02	8	970	74	<5	<20	47	0.02	<10	12	<10	<1	97
17	G37252	2.5	1.33	20	60	<5	0.72	1	18	110	1850	4.79	<10	1.29	1489	69	0.01	8	1140	48	10	<20	34	0.03	<10	27	<10	<1	257
18	G37253	1.5	1.84	20	80	<5	1.45	2	14	101	1563	4.82	<10	1.92	1789	54	0.01	8	1130	56	15	<20	127	0.03	<10	38	<10	<1	231
19	G37254	2.3	1.77	20	60	<5	0.71	4	13	84	1343	5.34	<10	1.70	1442	57	0.01	9	1180	200	5	<20	58	0.03	<10	39	<10	<1	317
20	G37255	2.0	1.98	20	80	<5	0.96	<1	15	76	1744	5.01	<10	1.87	1489	51	0.01	9	1320	46	15	<20	82	0.03	<10	39	<10	<1	206
21	G37256	1.5	1.76	15	50	<5	0.96	1	17	101	1247	5.33	<10	1.55	1080	67	0.02	10	1230	40	5	<20	48	0.03	<10	33	<10	<1	257
22	G37257	1.5	1.25	5	45	<5	1.34	1	15	105	1266	4.52	<10	1.24	1286	61	0.02	10	1300	56	<5	<20	55	0.03	<10	26	<10	<1	161
23	G37258	1.6	0.93	10	40	<5	1.55	1	15	117	1469	4.54	<10	1.10	1547	137	0.02	9	1100	70	5	<20	50	0.03	<10	21	<10	<1	157
24	G37259	2.1	0.55	15	45	<5	0.41	1	19	123	1889	6.42	<10	0.30	237	116	0.02	12	1220	34	<5	<20	23	0.02	<10	13	<10	<1	122
25	G37260	2.3	0.38	25	35	<5	0.60	1	14	132	1641	4.98	<10	0.21	344	54	0.02	12	1140	64	<5	<20	28	0.02	<10	9	<10	<1	104

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37261	3.7	1.09	60	70	<5	0.74	3	17	58	3346	3.90	20	0.47	270	217	0.03	14	340	134	40	<20	30	0.03	<10	43	<10	5	168
27	G37262	2.0	0.58	20	35	<5	1.42	<1	12	108	1569	3.18	<10	0.88	1231	99	0.02	15	700	30	10	<20	33	0.02	<10	9	<10	<1	117
28	G37263	2.5	0.50	20	35	<5	0.89	<1	14	152	1401	4.10	<10	0.58	807	58	0.02	14	650	38	<5	<20	30	0.02	<10	8	<10	<1	121
29	G37264	2.8	0.40	10	35	<5	0.72	2	14	137	1796	3.77	<10	0.42	630	89	0.02	17	580	30	5	<20	29	0.01	<10	6	<10	<1	149
30	G37265	2.8	0.38	10	35	<5	0.78	2	15	139	1779	4.30	<10	0.41	706	71	0.02	14	440	44	<5	<20	25	0.02	<10	6	<10	<1	163
31	G37266	2.2	0.62	10	35	<5	0.78	1	14	123	1302	4.08	<10	0.63	749	65	0.02	17	690	52	<5	<20	27	0.02	<10	8	<10	<1	220
32	G37267	1.7	1.57	30	50	<5	0.93	<1	10	138	1421	3.54	<10	1.67	1139	77	0.02	15	600	54	10	<20	30	0.02	<10	18	<10	<1	326
33	G37268	1.8	0.41	20	30	<5	0.47	1	13	147	1978	4.14	<10	0.31	440	94	0.02	11	530	58	<5	<20	23	0.01	<10	7	<10	<1	127
34	G37269	1.7	0.33	5	30	<5	0.15	<1	14	142	1359	4.39	<10	0.09	77	128	0.02	12	650	40	<5	<20	25	0.01	<10	6	<10	<1	66
35	G37270	1.9	0.38	25	35	<5	0.13	1	16	173	1643	5.03	<10	0.10	74	118	0.03	20	570	38	<5	<20	27	0.02	<10	6	<10	<1	92
QC DATA:																													
Repeat:																													
1	G37236	1.3	0.87	20	70	<5	0.83	<1	13	115	891	4.39	<10	1.55	1543	71	0.01	6	1290	30	10	<20	48	0.03	<10	24	<10	<1	169
10	G37245	1.9	0.44	20	40	<5	0.50	1	15	142	1364	4.62	<10	0.26	280	53	0.01	10	1030	38	<5	<20	39	0.01	<10	10	<10	<1	76
19	G37254	2.2	1.80	15	55	<5	0.72	4	14	90	1342	5.41	<10	1.71	1454	61	0.01	8	1200	208	5	<20	59	0.03	<10	40	<10	<1	323
Resplit:																													
1	G37236	1.4	0.84	20	60	<5	0.74	<1	13	108	860	4.03	<10	1.49	1533	77	0.01	9	1180	28	10	<20	39	0.02	<10	21	<10	<1	167
Standard:																													
Pb113		11.4	0.26	45	65	<5	1.70	38	2	5	2238	1.04	<10	0.09	1436	75	0.03	2	80	5450	20	<20	76	0.01	<10	7	10	<1	6935

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl/jl
df/7297S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5543

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

12-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07075
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37271	0.54	0.016
2	G37272	0.85	0.025
3	G37273	0.46	0.013
4	G37274	0.54	0.016
5	G37275	0.94	0.027
6	G37276	1.11	0.032
7	G37277	0.90	0.026
8	G37278	1.88	0.055
9	G37279	0.71	0.021
10	G37280	1.81	0.053
11	G37281	0.49	0.014
12	G37282	0.72	0.021
13	G37283	0.70	0.020
14	G37284	0.70	0.020
15	G37285	0.76	0.022
16	G37286	1.24	0.036
17	G37287	0.49	0.014
18	G37288	0.38	0.011
19	G37289	0.40	0.012
20	G37290	<0.03	<0.001
21	G37291	0.47	0.014
22	G37292	0.86	0.025
23	G37293	1.22	0.036
24	G37294	0.86	0.025
25	G37295	1.06	0.031
26	G37296	0.86	0.025

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7 - 5543

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	G37297	0.39	0.011
28	G37298	0.37	0.011
29	G37299	0.58	0.017
30	G37300	0.50	0.015
31	G37301	0.54	0.016
32	G37302	0.68	0.020
33	G37303	0.77	0.022
34	G37304	1.06	0.031
35	G37305	0.77	0.022
QC DATA:			
Repeat:			
1	G37271	0.60	0.017
6	G37276	0.94	0.027
8	G37278	1.79	0.052
16	G37286	1.30	0.038
19	G37289	0.42	0.012
23	G37293	1.07	0.031
34	G37304	1.02	0.030
Resplits:			
1	G37271	0.72	0.021
Standard:			
OXI54		1.88	0.055

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
XLS/07

18-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5543

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07075
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37271	1.6	0.51	65	25	<5	0.10	1	9	236	1011	3.79	<10	0.25	173	172	0.02	10	470	194	5	<20	22	<0.01	<10	6	<10	<1	123
2	G37272	1.6	0.55	70	30	<5	0.17	4	11	156	1477	6.27	<10	0.21	202	169	0.02	13	1060	24	<5	<20	17	<0.01	<10	8	<10	<1	215
3	G37273	2.2	0.37	170	30	<5	0.07	2	10	172	1197	4.15	<10	0.09	123	210	0.02	13	420	32	30	<20	11	<0.01	<10	4	<10	<1	74
4	G37274	2.0	0.48	75	30	<5	0.16	<1	9	186	1077	3.21	<10	0.14	114	137	0.02	17	850	42	15	<20	18	<0.01	<10	5	<10	<1	43
5	G37275	1.6	0.50	20	30	<5	0.29	1	14	109	1161	5.20	<10	0.14	176	65	0.03	16	1650	20	<5	<20	39	<0.01	<10	8	<10	2	69
6	G37276	1.8	0.53	45	40	<5	0.21	1	19	140	1382	5.92	<10	0.21	284	180	0.02	21	1010	40	<5	<20	16	0.02	<10	9	<10	<1	196
7	G37277	2.4	0.62	30	30	<5	0.22	7	17	129	1769	6.88	<10	0.25	262	132	0.02	15	1310	30	<5	<20	18	<0.01	<10	9	<10	1	655
8	G37278	5.7	0.47	300	70	<5	0.51	17	16	112	1369	>10	<10	0.04	89	109	0.03	17	2570	168	25	<20	25	0.04	<10	6	<10	<1	2081
9	G37279	2.5	0.54	135	30	<5	0.16	1	11	183	1503	5.31	<10	0.17	158	193	0.03	13	940	40	15	<20	15	<0.01	<10	7	<10	<1	65
10	G37280	3.9	1.15	35	45	<5	0.97	2	19	55	8680	4.08	20	0.61	215	584	0.04	61	650	56	20	<20	60	0.04	<10	38	<10	8	71
11	G37281	2.6	0.43	240	30	<5	0.13	1	11	172	1744	4.74	<10	0.12	116	125	0.02	9	720	28	25	<20	14	<0.01	<10	5	<10	<1	74
12	G37282	1.9	0.44	115	30	<5	0.15	1	9	166	1417	4.92	<10	0.12	131	111	0.03	12	850	30	10	<20	19	<0.01	<10	7	<10	<1	46
13	G37283	2.2	0.55	120	35	<5	0.13	<1	11	157	1349	4.35	<10	0.17	152	139	0.03	16	710	34	15	<20	19	<0.01	<10	8	<10	<1	63
14	G37284	3.0	0.49	175	30	<5	0.10	2	11	172	1843	4.38	<10	0.16	144	75	0.02	13	590	30	25	<20	17	<0.01	<10	7	<10	<1	90
15	G37285	1.7	0.70	65	30	<5	0.21	1	16	169	1214	5.61	<10	0.28	199	176	0.03	14	1210	40	5	<20	26	<0.01	<10	10	<10	2	122
16	G37286	1.3	0.48	75	50	<5	0.22	<1	18	130	1587	6.28	<10	0.12	141	107	0.03	21	1090	40	<5	<20	22	0.02	<10	9	<10	<1	87
17	G37287	0.9	0.40	165	30	5	0.22	1	12	147	1005	5.32	<10	0.07	68	141	0.03	13	1290	22	15	<20	18	<0.01	<10	8	<10	1	69
18	G37288	1.1	0.30	385	30	<5	0.11	<1	10	145	1006	3.88	<10	<0.01	23	99	0.03	12	640	14	35	<20	17	<0.01	<10	6	<10	1	83
19	G37289	0.9	0.32	275	30	<5	0.16	1	14	143	1363	5.22	<10	0.03	30	89	0.03	13	880	32	25	<20	16	<0.01	<10	7	<10	<1	73
20	G37290	<0.2	1.17	10	235	<5	0.60	<1	7	91	4	2.17	<10	0.60	563	1	0.11	7	990	10	<5	<20	92	0.14	<10	42	<10	4	44
21	G37291	0.5	0.48	45	35	<5	0.26	<1	12	125	1528	5.17	<10	0.11	75	75	0.03	13	1510	24	<5	<20	20	<0.01	<10	9	<10	1	29
22	G37292	1.0	0.41	310	25	<5	0.20	1	12	163	1521	5.85	<10	0.09	107	128	0.03	10	1090	44	40	<20	24	<0.01	<10	7	<10	<1	92
23	G37293	1.7	0.38	230	40	<5	0.23	3	18	125	1601	6.26	<10	0.06	89	223	0.03	11	1150	42	35	<20	26	0.02	<10	8	<10	<1	99
24	G37294	1.5	0.50	55	30	<5	0.29	2	14	142	1695	6.43	<10	0.15	125	100	0.03	2	1750	44	15	<20	22	<0.01	<10	10	<10	1	64
25	G37295	1.6	0.54	60	30	<5	0.30	2	15	157	1625	6.31	<10	0.15	119	120	0.03	2	1770	48	10	<20	22	<0.01	<10	10	<10	1	67

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37296	1.2	0.51	65	30	<5	0.32	1	13	121	1501	6.45	<10	0.12	89	130	0.03	1	1900	60	10	<20	23	<0.01	<10	9	<10	1	55
27	G37297	0.7	0.51	15	30	<5	0.25	<1	10	146	1161	4.46	<10	0.09	60	137	0.03	3	1560	42	<5	<20	19	<0.01	<10	9	<10	1	32
28	G37298	1.3	0.25	120	30	10	0.20	1	10	110	566	3.95	<10	<0.01	21	183	0.04	2	1230	16	25	<20	23	<0.01	<10	5	<10	2	41
29	G37299	0.9	0.40	15	30	<5	0.21	<1	11	115	1517	4.43	<10	0.06	48	162	0.03	2	1340	24	<5	<20	18	<0.01	<10	8	<10	1	17
30	G37300	1.3	0.61	10	30	<5	0.24	<1	14	133	1311	4.99	<10	0.19	122	99	0.03	2	1420	66	<5	<20	16	<0.01	<10	10	<10	1	39
31	G37301	1.1	0.59	10	30	<5	0.31	<1	12	118	1213	5.13	<10	0.11	104	215	0.03	2	1810	38	<5	<20	22	<0.01	<10	9	<10	2	29
32	G37302	1.0	0.45	10	25	<5	0.26	<1	12	116	1400	5.62	<10	0.08	71	153	0.04	2	1440	32	<5	<20	21	<0.01	<10	8	<10	1	28
33	G37303	1.2	0.52	15	25	<5	0.30	<1	14	152	1238	6.22	<10	0.09	87	280	0.04	2	1790	52	<5	<20	24	<0.01	<10	11	<10	2	31
34	G37304	1.4	0.53	45	55	<5	0.34	<1	21	114	1409	7.18	<10	0.07	75	246	0.04	6	1690	74	<5	<20	34	0.03	<10	12	<10	<1	44
35	G37305	1.7	0.58	55	30	<5	0.36	1	12	150	1190	6.10	<10	0.09	76	308	0.04	2	2170	48	15	<20	30	<0.01	<10	12	<10	2	58
QC DATA:																													
Repeat:																													
1	G37271	1.7	0.53	65	30	<5	0.10	1	9	251	1044	3.70	<10	0.25	177	176	0.02	11	490	192	5	<20	23	<0.01	<10	7	<10	<1	119
6	G37276	1.8	0.53	30	45	<5	0.20	1	19	138	1356	5.74	<10	0.21	279	163	0.02	21	980	36	<5	<20	23	0.02	<10	8	<10	<1	188
11	G37281	2.6	0.44	230	30	<5	0.12	1	10	170	1758	4.57	<10	0.12	114	126	0.02	9	690	28	25	<20	14	<0.01	<10	6	<10	<1	72
19	G37289	0.9	0.34	270	30	<5	0.15	1	14	148	1346	5.06	<10	0.03	31	90	0.03	12	870	34	20	<20	16	<0.01	<10	7	<10	<1	72
Resplit:																													
1	G37271	1.5	0.50	55	30	<5	0.10	2	11	220	1096	3.92	<10	0.23	158	175	0.02	10	530	174	<5	<20	22	<0.01	<10	8	<10	<1	123
Standard:																													
Pb113		11.0	0.31	55	65	<5	1.63	37	2	1	2411	1.01	<10	0.11	1486	56	0.02	<1	220	5438	5	<20	117	0.01	<10	9	<10	1	6921

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/n5541S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5544

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07077
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35181	1.44	0.042
2	G35182	1.62	0.047
3	G35183	1.08	0.031
4	G35184	0.70	0.020
5	G35185	0.75	0.022
6	G35186	1.81	0.053
7	G35187	2.15	0.063
8	G35188	1.15	0.034
9	G35189	1.20	0.035
10	G35190	0.76	0.022
11	G35191	1.82	0.053
12	G35192	0.71	0.021
13	G35193	0.96	0.028
14	G35194	0.95	0.028
15	G35195	0.98	0.029
16	G35196	0.48	0.014
17	G35197	0.73	0.021
18	G35198	1.33	0.039
19	G35199	1.47	0.043
20	G35200	0.68	0.020
21	G35201	<0.03	<0.001
22	G35202	0.56	0.016
23	G35203	1.59	0.046
24	G35204	0.69	0.020
25	G35205	0.42	0.012
26	G35206	1.02	0.030
27	G35207	0.96	0.028
28	G35208	1.10	0.032

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5544 17-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G35209	0.89	0.026
30	G35210	0.94	0.027
31	G35211	0.64	0.019
32	G35212	0.65	0.019
33	G35213	0.56	0.016
34	G35214	0.50	0.015
35	G35215	1.00	0.029

QC DATA:

Repeat:

1	G35181	1.38	0.040
2	G35182	1.59	0.046
7	G35187	2.27	0.066
10	G35190	0.74	0.022
18	G35198	1.24	0.036
19	G35199	1.44	0.042
23	G35203	1.68	0.049

Resplits:

1	G35181	1.28	0.037

Standard:

SI25		1.79	0.052

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

18-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5544

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07077
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35181	4.1	0.55	15	30	<5	0.23	2	8	151	2583	6.34	<10	0.34	336	10	0.01	<1	530	74	<5	<20	39	<0.01	<10	24	<10	<1	128
2	G35182	4.8	0.42	25	30	<5	0.12	2	8	214	2999	6.06	<10	0.19	144	12	0.01	2	500	76	<5	<20	20	<0.01	<10	24	<10	<1	114
3	G35183	4.4	0.50	25	25	<5	0.13	6	8	197	2395	5.23	<10	0.29	213	14	0.01	3	430	86	<5	<20	20	<0.01	<10	21	<10	<1	216
4	G35184	3.2	0.35	10	25	<5	0.30	3	9	163	2232	6.32	<10	0.10	142	10	0.01	1	480	108	<5	<20	30	<0.01	<10	24	<10	<1	104
5	G35185	2.6	0.33	15	25	<5	0.57	5	11	200	2562	5.94	<10	0.10	237	20	0.01	2	530	228	<5	<20	35	<0.01	<10	17	<10	<1	267
6	G35186	3.4	0.46	30	25	<5	0.43	3	8	165	2657	6.30	<10	0.19	241	22	0.01	1	620	66	<5	<20	36	<0.01	<10	22	<10	<1	134
7	G35187	7.7	0.66	30	30	<5	0.19	2	7	202	2717	6.54	<10	0.35	336	16	0.01	2	530	72	<5	<20	15	<0.01	<10	28	<10	<1	111
8	G35188	5.6	0.31	20	30	<5	0.71	3	11	184	2896	6.04	<10	0.07	362	28	0.01	2	520	66	15	<20	38	<0.01	<10	18	<10	1	159
9	G35189	3.3	0.46	5	25	<5	0.44	2	10	183	2855	5.82	<10	0.21	305	13	0.01	2	590	70	<5	<20	32	<0.01	<10	19	<10	1	80
10	G35190	3.9	0.28	10	30	<5	0.24	3	13	167	3298	5.82	<10	0.05	140	10	0.01	1	560	82	<5	<20	26	<0.01	<10	16	<10	<1	69
11	G35191	3.9	1.16	35	50	<5	0.91	2	19	55	8599	4.03	20	0.59	211	543	0.04	61	660	56	20	<20	56	0.04	<10	39	<10	7	79
12	G35192	3.7	0.65	10	30	<5	0.36	2	7	178	2507	5.62	<10	0.38	360	14	0.01	2	550	66	<5	<20	25	<0.01	<10	25	<10	<1	128
13	G35193	2.8	0.42	10	30	<5	0.57	1	9	147	2418	4.86	<10	0.20	371	14	<0.01	1	440	52	<5	<20	36	<0.01	<10	18	<10	<1	52
14	G35194	3.0	0.33	10	25	<5	0.81	1	9	164	2626	5.37	<10	0.10	423	12	0.01	2	540	54	<5	<20	37	<0.01	<10	18	<10	2	29
15	G35195	3.4	0.76	40	30	<5	0.22	1	7	150	2192	5.42	<10	0.46	266	18	0.01	1	640	28	<5	<20	43	<0.01	<10	28	<10	1	85
16	G35196	5.7	0.32	10	35	<5	0.94	1	16	167	3155	6.32	<10	0.44	808	43	0.01	1	360	32	<5	<20	75	<0.01	<10	23	<10	2	15
17	G35197	4.6	0.25	75	30	<5	1.58	2	5	142	1746	5.48	<10	0.65	1181	13	0.01	1	550	24	10	<20	93	<0.01	<10	21	<10	3	23
18	G35198	12.9	0.26	270	35	<5	0.30	3	11	175	5425	7.30	<10	0.04	213	8	0.01	1	660	34	40	<20	37	<0.01	<10	20	<10	1	42
19	G35199	3.4	0.46	70	30	<5	0.44	1	6	148	1609	6.34	<10	0.25	329	9	0.01	<1	790	32	10	<20	45	<0.01	<10	27	<10	2	41
20	G35200	3.6	0.34	40	30	<5	0.54	1	12	199	1829	6.63	<10	0.24	431	26	0.01	2	430	26	5	<20	36	<0.01	<10	29	<10	1	28
21	G35201	<0.2	1.24	5	235	5	0.65	<1	7	90	8	2.20	<10	0.60	600	2	0.12	7	960	16	<5	<20	90	0.15	<10	44	<10	5	47
22	G35202	5.1	0.35	55	35	<5	1.25	1	5	150	2550	4.70	<10	0.35	724	12	0.01	1	500	24	10	<20	131	<0.01	<10	32	<10	2	28
23	G35203	3.4	0.53	15	30	<5	0.89	1	6	154	2911	5.35	<10	0.34	611	11	0.01	<1	450	28	<5	<20	48	<0.01	<10	41	<10	1	70
24	G35204	3.1	0.34	5	30	<5	0.38	2	7	219	3132	5.09	<10	0.21	330	11	0.01	2	270	34	<5	<20	37	<0.01	<10	38	<10	<1	98
25	G35205	3.0	0.14	<5	25	<5	0.31	4	8	165	2935	4.80	<10	0.07	246	13	0.01	2	200	58	<5	<20	66	<0.01	<10	26	<10	<1	169

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35206	1.9	0.80	50	30	<5	0.43	1	5	141	1617	5.98	<10	0.52	622	11	0.01	<1	540	34	<5	<20	29	<0.01	<10	50	<10	1	102
27	G35207	2.8	0.49	20	30	<5	0.53	1	10	169	2676	5.64	<10	0.27	470	21	0.01	1	520	54	<5	<20	32	<0.01	<10	41	<10	1	49
28	G35208	1.8	0.67	40	30	<5	0.65	2	10	157	1728	6.11	<10	0.44	624	19	0.01	1	600	34	<5	<20	33	<0.01	<10	43	<10	2	66
29	G35209	2.1	0.73	30	35	<5	0.75	1	7	156	2089	5.12	<10	0.47	794	17	0.01	1	580	22	<5	<20	49	<0.01	<10	48	<10	2	70
30	G35210	2.2	0.57	15	40	<5	0.70	1	7	161	2505	5.72	<10	0.35	646	11	0.01	<1	460	30	<5	<20	78	<0.01	<10	80	<10	2	80
31	G35211	1.4	0.57	5	35	<5	1.16	<1	7	128	1681	4.98	<10	0.30	911	9	0.01	<1	620	20	<5	<20	49	<0.01	<10	56	<10	3	60
32	G35212	2.8	0.58	5	30	<5	0.51	1	9	126	2255	5.42	<10	0.35	486	19	0.01	<1	660	26	<5	<20	55	<0.01	<10	50	<10	2	63
33	G35213	4.9	0.68	45	30	<5	0.62	1	19	120	2673	7.23	<10	0.46	611	11	0.02	<1	740	42	5	<20	41	<0.01	<10	48	<10	2	67
34	G35214	4.3	0.65	40	30	<5	0.60	1	25	129	2055	7.04	<10	0.44	603	7	0.01	<1	680	32	<5	<20	38	<0.01	<10	43	<10	2	62
35	G35215	2.0	0.69	20	30	<5	0.74	1	7	115	2041	5.25	<10	0.49	660	10	0.01	<1	670	20	<5	<20	48	<0.01	<10	54	<10	2	77
QC DATA:																													
Repeat:																													
1	G35181	3.9	0.56	15	25	<5	0.22	2	8	156	2606	6.40	<10	0.34	331	10	0.02	<1	540	66	<5	<20	39	<0.01	<10	24	<10	<1	120
10	G35190	3.9	0.27	5	25	<5	0.21	3	13	173	3326	5.94	<10	0.05	136	10	0.01	1	560	86	<5	<20	27	<0.01	<10	17	<10	<1	70
19	G35199	3.4	0.47	70	30	<5	0.44	1	6	149	1595	6.42	<10	0.26	332	8	0.01	<1	790	32	5	<20	49	<0.01	<10	29	<10	2	40
Resplit:																													
1	G35181	3.9	0.54	10	35	<5	0.25	2	9	160	2637	6.53	<10	0.34	353	20	0.01	<1	530	76	<5	<20	40	<0.01	<10	26	<10	1	133
Standard:																													
Pb113		11.4	0.29	45	60	<5	1.69	38	2	2	2266	1.03	<10	0.11	1542	68	0.02	<1	90	5452	5	<20	89	0.01	<10	12	<10	1	6984

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/n5541S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5547

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

18-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07076
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37306	0.70	0.020
2	G37307	0.74	0.022
3	G37308	0.62	0.018
4	G37309	0.73	0.021
5	G37310	0.59	0.017
6	G37311	1.19	0.035
7	G37312	0.91	0.027
8	G37313	0.80	0.023
9	G37314	0.82	0.024
10	G37315	0.62	0.018
11	G37316	0.59	0.017
12	G37317	1.39	0.041
13	G37318	0.79	0.023
14	G37319	<0.03	<0.001
15	G37320	0.65	0.019
16	G37321	0.81	0.024
17	G37322	0.55	0.016
18	G37323	0.60	0.017
19	G37324	0.23	0.007
20	G37325	0.24	0.007
21	G37326	0.25	0.007
22	G37327	0.86	0.025
23	G37328	0.59	0.017
24	G37329	1.83	0.053
25	G37330	0.79	0.023
26	G37331	0.86	0.025
27	G37332	0.82	0.024
28	G37333	0.65	0.019

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 5547 18-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G37334	0.74	0.022
30	G37335	0.83	0.024
31	G37336	0.78	0.023
32	G37337	0.67	0.020
33	G37338	0.65	0.019
34	G37339	0.36	0.010
35	G37340	0.95	0.028

QC DATA:

Repeat:

1	G37306	0.69	0.020
6	G37311	1.03	0.030
10	G37315	0.58	0.017
12	G37317	1.36	0.040
19	G37324	0.26	0.008
22	G37327	0.75	0.022

Resplits:

1	G37306	0.72	0.021

Standard:

SI25		1.83	0.053

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

18-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5547

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07076
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37306	1.0	0.56	10	30	<5	0.35	<1	16	152	1049	6.11	<10	0.10	96	223	0.04	5	1760	84	<5	<20	33	0.04	<10	10	<10	<1	38
2	G37307	1.4	0.50	10	30	<5	0.32	<1	17	142	1247	6.58	<10	0.09	121	122	0.03	8	1540	86	<5	<20	38	0.04	<10	9	<10	<1	33
3	G37308	1.1	0.56	10	25	<5	0.34	<1	14	135	946	4.98	<10	0.13	129	131	0.03	5	1640	68	<5	<20	132	0.03	<10	9	<10	<1	45
4	G37309	1.1	0.54	5	25	<5	0.33	<1	15	144	1043	5.23	<10	0.13	136	296	0.03	6	1590	56	<5	<20	145	0.03	<10	9	<10	<1	49
5	G37310	0.7	0.52	25	25	<5	0.28	<1	16	149	659	6.00	<10	0.13	138	300	0.02	6	1290	94	<5	<20	163	0.04	<10	8	<10	<1	65
6	G37311	1.1	0.61	25	30	<5	0.39	<1	18	125	1142	5.67	<10	0.12	104	195	0.03	6	1970	52	<5	<20	30	0.03	<10	11	<10	<1	58
7	G37312	2.0	0.50	150	35	<5	0.34	2	17	132	1336	5.98	<10	0.07	80	192	0.03	6	1690	56	100	<20	29	0.04	<10	10	<10	<1	115
8	G37313	1.4	0.55	75	35	<5	0.36	2	20	136	1173	7.79	<10	0.12	117	118	0.03	8	1800	84	35	<20	45	0.05	<10	10	<10	<1	77
9	G37314	0.9	0.63	20	30	<5	0.33	2	19	121	1188	6.23	<10	0.17	153	411	0.03	9	1600	58	<5	<20	50	0.03	<10	12	<10	<1	46
10	G37315	1.6	0.44	70	35	<5	0.32	1	18	143	1352	5.60	<10	0.07	90	81	0.03	12	1570	82	20	<20	34	0.03	<10	7	<10	<1	60
11	G37316	0.6	0.77	30	35	<5	0.26	<1	16	114	888	4.31	<10	0.31	223	154	0.03	19	1330	26	<5	<20	29	0.03	<10	10	<10	<1	96
12	G37317	0.7	0.48	25	35	<5	0.27	<1	18	129	1113	5.88	<10	0.06	81	135	0.03	23	1350	24	<5	<20	27	0.03	<10	6	<10	<1	29
13	G37318	1.1	0.38	30	35	<5	0.25	<1	17	106	1141	5.59	<10	0.02	74	189	0.03	21	1250	24	<5	<20	21	0.04	<10	6	<10	<1	27
14	G37319	<0.2	1.12	20	260	30	0.63	<1	7	91	6	2.25	<10	0.61	566	2	0.11	6	990	16	<5	<20	93	0.17	<10	49	<10	<1	46
15	G37320	1.1	0.50	15	35	<5	0.21	<1	18	122	945	5.46	<10	0.10	99	91	0.03	20	1020	30	<5	<20	21	0.03	<10	7	<10	<1	43
16	G37321	1.2	0.49	30	35	<5	0.27	<1	17	142	956	5.81	<10	0.09	102	122	0.03	19	1320	48	<5	<20	26	0.04	<10	7	<10	<1	53
17	G37322	1.2	0.68	30	30	<5	0.23	1	16	106	1021	5.35	<10	0.20	143	175	0.03	19	1120	46	<5	<20	26	0.03	<10	11	<10	<1	100
18	G37323	0.9	0.60	45	35	<5	0.30	1	12	149	1452	4.46	<10	0.16	188	165	0.03	15	1400	40	<5	<20	34	0.03	<10	8	<10	<1	92
19	G37324	0.5	0.40	15	30	<5	0.10	1	15	172	858	4.54	<10	0.09	112	518	0.02	13	440	32	<5	<20	37	0.02	<10	5	<10	<1	67
20	G37325	1.2	0.30	110	30	<5	0.09	2	16	196	523	6.09	<10	<0.01	51	100	0.02	13	400	66	15	<20	35	0.04	<10	4	<10	<1	57
21	G37326	0.7	0.54	30	35	<5	0.08	1	12	151	895	6.21	<10	0.15	141	164	0.02	12	330	54	<5	<20	17	0.04	<10	7	<10	<1	93
22	G37327	0.8	0.62	10	35	<5	0.13	2	17	144	1248	7.02	<10	0.20	169	151	0.02	14	600	58	<5	<20	15	0.04	<10	8	<10	<1	139
23	G37328	0.7	0.52	5	30	<5	0.09	1	15	142	569	6.61	<10	0.13	121	106	0.02	12	400	102	<5	<20	15	0.05	<10	6	<10	<1	89
24	G37329	4.1	1.15	45	50	<5	1.08	2	23	64	8640	4.21	<10	0.63	209	649	0.05	65	480	78	25	<20	59	0.05	<10	46	<10	6	77
25	G37330	1.2	0.52	10	30	<5	0.19	<1	21	159	1054	6.36	<10	0.09	107	159	0.03	17	860	44	<5	<20	13	0.03	<10	7	<10	<1	58

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37331	1.3	0.63	15	35	<5	0.18	<1	19	114	948	6.91	<10	0.11	119	147	0.04	19	840	32	<5	<20	19	0.04	<10	8	<10	<1	57
27	G37332	1.5	0.58	30	35	<5	0.36	<1	20	119	955	6.44	<10	0.07	102	225	0.04	16	1810	52	<5	<20	27	0.04	<10	10	<10	<1	46
28	G37333	0.8	0.55	20	30	<5	0.43	<1	16	78	629	5.41	<10	0.09	106	101	0.03	6	2160	24	<5	<20	24	0.03	<10	9	<10	2	55
29	G37334	1.1	0.60	25	35	<5	0.43	<1	17	104	660	5.73	<10	0.10	109	216	0.04	7	2160	26	<5	<20	26	0.03	<10	10	<10	2	56
30	G37335	1.0	0.81	30	35	<5	0.36	2	16	65	580	5.44	<10	0.29	225	230	0.02	8	1850	34	10	<20	20	0.02	<10	16	<10	2	156
31	G37336	1.1	0.56	15	40	<5	0.41	<1	14	59	465	4.46	<10	0.18	159	60	0.02	4	1890	30	<5	<20	20	0.03	<10	12	<10	2	119
32	G37337	1.3	0.74	10	35	<5	0.43	<1	20	101	755	5.44	<10	0.19	156	167	0.03	8	2180	64	<5	<20	34	0.03	<10	13	<10	2	96
33	G37338	0.9	0.71	10	35	<5	0.30	2	18	137	693	5.08	<10	0.19	152	95	0.04	20	1500	68	<5	<20	29	0.03	<10	10	<10	<1	108
34	G37339	1.1	0.81	15	35	<5	0.50	<1	15	130	547	4.50	<10	0.24	177	62	0.03	22	2550	80	<5	<20	26	0.03	<10	11	<10	2	104
35	G37340	0.9	0.79	5	35	<5	0.37	<1	16	125	571	4.76	<10	0.21	137	223	0.04	20	1910	54	<5	<20	28	0.03	<10	11	<10	1	72
QC DATA:																													
Repeat:																													
1	G37306	1.0	0.63	10	40	<5	0.35	<1	16	160	1059	6.08	<10	0.11	96	230	0.04	7	1740	82	<5	<20	34	0.04	<10	11	<10	<1	37
10	G37315	1.6	0.47	70	35	<5	0.32	2	18	149	1353	5.59	<10	0.08	93	86	0.03	11	1560	86	25	<20	37	0.03	<10	8	<10	<1	61
19	G37324	0.5	0.42	20	25	<5	0.10	<1	16	180	859	4.59	<10	0.09	113	499	0.02	10	420	32	<5	<20	40	0.03	<10	5	<10	<1	69
Resplit:																													
1	G37306	1.2	0.65	15	35	<5	0.39	<1	18	147	1253	6.85	<10	0.11	101	259	0.04	6	1940	92	<5	<20	36	0.04	<10	11	<10	<1	43
Standard:																													
Pb113		11.0	0.31	45	70	<5	1.81	42	3	6	2300	1.18	<10	0.11	1517	72	0.02	2	80	5440	20	<20	77	0.02	<10	8	<10	<1	6902

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
dl/5545
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5548

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

25-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07078
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37341	0.38	0.011
2	G37342	0.36	0.010
3	G37343	0.50	0.015
4	G37344	0.43	0.013
5	G37345	0.34	0.010
6	G37346	0.42	0.012
7	G37347	0.29	0.008
8	G37348	0.47	0.014
9	G37349	0.30	0.009
10	G37350	0.24	0.007
11	G37351	0.35	0.010
12	G37352	0.30	0.009
13	G37353	0.57	0.017
14	G37354	0.50	0.015
15	G37355	0.38	0.011
16	G37356	0.28	0.008
17	G37357	0.31	0.009
18	G37358	0.18	0.005
19	G37359	0.23	0.007
20	G37360	0.23	0.007
21	G37361	0.36	0.010
22	G37362	0.33	0.010
23	G37363	0.26	0.008
24	G37364	0.36	0.010
25	G37365	0.30	0.009

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS07-5548 25-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	G37366	0.31	0.009
27	G37367	0.21	0.006
28	G37368	0.22	0.006
29	G37369	<0.03	<0.001
30	G37370	0.16	0.005
31	G37371	0.18	0.005
32	G37372	0.20	0.006
33	G37373	0.31	0.009
34	G37374	0.36	0.010
35	G37375	0.19	0.006

QC DATA:

Repeat:

1	G37341	0.39	0.011
10	G37350	0.24	0.007
19	G37359	0.23	0.007

Resplits:

1	G37341	0.41	0.012

Standard:

SI25		1.83	0.053

AU: 30g FA/AA-Finish

JJ/dc
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

25-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5548

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07078
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37341	0.8	0.61	<5	50	<5	0.26	1	14	126	652	3.68	<10	0.17	92	192	0.03	20	1230	46	<5	<20	32	0.01	<10	8	<10	<1	37
2	G37342	0.6	0.94	<5	45	<5	0.31	<1	13	100	492	3.84	<10	0.35	205	291	0.03	10	1490	44	<5	<20	34	0.02	<10	16	<10	1	62
3	G37343	0.6	1.26	<5	50	<5	0.41	1	17	76	521	5.45	<10	0.53	268	95	0.03	7	2000	26	<5	<20	30	0.02	<10	22	<10	1	84
4	G37344	0.6	1.37	<5	50	<5	0.42	<1	16	71	477	5.24	<10	0.59	265	69	0.03	3	2070	48	<5	<20	32	0.03	<10	25	<10	2	76
5	G37345	0.6	1.33	<5	50	<5	0.40	1	14	73	353	5.18	<10	0.57	257	107	0.03	6	1970	84	10	<20	29	0.02	<10	24	<10	1	66
6	G37346	0.5	1.36	<5	50	<5	0.39	2	15	84	399	4.51	<10	0.61	262	60	0.03	7	1950	58	10	<20	30	0.02	<10	30	<10	2	69
7	G37347	0.4	1.54	<5	50	<5	0.42	1	14	70	355	4.66	<10	0.72	286	44	0.03	6	2070	42	10	<20	30	0.02	<10	35	<10	2	80
8	G37348	0.6	1.26	<5	50	<5	0.40	1	15	83	497	4.80	<10	0.52	187	24	0.03	7	1990	58	10	<20	31	0.02	<10	22	<10	1	55
9	G37349	0.6	1.09	<5	50	<5	0.39	2	15	81	304	4.80	<10	0.41	152	102	0.04	7	1920	88	10	<20	33	0.02	<10	17	<10	<1	43
10	G37350	0.5	1.11	<5	50	<5	0.39	2	15	91	240	5.58	<10	0.41	132	65	0.03	8	1920	88	10	<20	31	0.02	<10	19	<10	<1	43
11	G37351	0.4	1.41	<5	50	<5	0.41	2	15	82	408	4.21	<10	0.57	175	52	0.04	8	2030	42	20	<20	34	0.01	<10	26	<10	2	61
12	G37352	0.3	1.01	<5	45	<5	0.46	1	14	70	324	4.67	<10	0.32	126	16	0.04	4	2300	34	<5	<20	30	0.02	<10	15	<10	<1	37
13	G37353	0.6	1.24	<5	55	<5	0.45	2	19	90	660	5.64	<10	0.47	183	32	0.04	8	2190	46	10	<20	30	0.02	<10	21	<10	<1	56
14	G37354	0.6	1.38	<5	50	<5	0.46	1	18	79	496	5.43	<10	0.56	213	67	0.04	4	2220	58	<5	<20	34	0.03	<10	23	<10	1	63
15	G37355	0.7	1.00	<5	50	<5	0.49	2	18	80	448	6.13	<10	0.32	122	26	0.04	9	2360	78	10	<20	35	0.03	<10	16	<10	<1	35
16	G37356	3.1	1.20	40	50	<5	0.96	3	20	60	2684	3.39	20	0.64	191	201	0.03	10	470	60	15	<20	66	0.04	<10	46	<10	7	266
17	G37357	0.3	1.20	<5	50	<5	0.42	1	15	77	341	4.71	<10	0.47	169	84	0.04	6	2000	36	10	<20	32	0.02	<10	16	<10	<1	52
18	G37358	0.4	1.05	<5	55	5	0.44	1	15	74	227	4.59	<10	0.40	147	27	0.04	6	2150	38	<5	<20	37	0.02	<10	15	<10	<1	47
19	G37359	0.4	1.00	<5	50	<5	0.39	1	13	82	325	3.79	<10	0.37	118	45	0.04	17	1870	38	5	<20	41	0.02	<10	19	<10	<1	43
20	G37360	0.4	1.29	<5	45	<5	0.40	1	16	96	229	4.44	<10	0.49	161	42	0.04	13	1930	42	<5	<20	44	0.02	<10	22	<10	<1	61
21	G37361	0.7	1.04	<5	50	<5	0.41	2	17	82	292	5.66	<10	0.38	141	51	0.03	7	1960	86	<5	<20	34	0.02	<10	17	<10	<1	58
22	G37362	0.4	1.10	<5	50	15	0.46	2	15	64	178	5.24	<10	0.43	175	81	0.03	6	2250	38	10	<20	34	0.02	<10	17	<10	1	67
23	G37363	0.3	1.25	<5	45	<5	0.41	1	17	57	243	4.86	<10	0.57	235	27	0.03	6	1990	26	10	<20	27	0.02	<10	26	<10	3	89
24	G37364	0.4	1.12	<5	55	<5	0.40	2	15	66	287	5.54	<10	0.50	243	36	0.03	8	1950	28	15	<20	27	0.02	<10	25	<10	2	85
25	G37365	0.3	0.81	<5	55	<5	0.45	1	17	55	272	5.31	<10	0.31	180	12	0.03	6	2220	22	<5	<20	28	0.02	<10	13	<10	3	65

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37366	0.4	0.71	<5	45	<5	0.40	1	17	82	191	5.29	<10	0.23	132	14	0.03	8	1910	22	<5	<20	23	0.02	<10	11	<10	<1	55
27	G37367	0.3	0.86	<5	50	5	0.49	1	12	66	136	4.75	<10	0.33	176	23	0.03	7	2400	22	<5	<20	27	0.02	<10	14	<10	<1	83
28	G37368	0.3	0.57	<5	60	10	0.48	2	15	57	150	5.05	<10	0.20	123	18	0.03	9	2270	22	15	<20	30	0.02	<10	10	<10	2	62
29	G37369	<0.2	1.02	5	260	5	0.57	<1	6	109	5	2.04	<10	0.59	512	5	0.09	7	890	18	10	<20	96	0.10	<10	44	<10	5	38
30	G37370	0.2	0.56	<5	50	<5	0.43	1	13	62	122	4.29	<10	0.17	91	10	0.03	4	2110	20	<5	<20	25	0.02	<10	9	<10	<1	51
31	G37371	0.3	0.43	<5	50	10	0.44	1	15	73	110	5.06	<10	0.06	48	10	0.03	4	2120	28	<5	<20	25	0.02	<10	8	<10	<1	29
32	G37372	0.2	0.66	<5	55	20	0.39	2	15	65	126	5.57	<10	0.21	112	29	0.03	7	1860	30	5	<20	31	0.02	<10	11	<10	<1	79
33	G37373	0.3	0.78	<5	60	<5	0.45	3	18	69	281	5.32	<10	0.32	181	26	0.03	13	2150	20	35	<20	29	0.01	<10	15	<10	2	112
34	G37374	0.2	0.80	<5	65	5	0.48	1	15	53	223	4.94	<10	0.34	187	57	0.03	6	2330	26	<5	<20	31	0.02	<10	18	<10	3	121
35	G37375	0.3	0.48	<5	55	<5	0.39	2	16	76	148	4.76	<10	0.07	54	24	0.03	6	1870	32	<5	<20	22	0.02	<10	9	<10	<1	52
QC DATA:																													
Repeat:																													
1	G37341	0.8	0.54	<5	45	<5	0.25	<1	14	118	652	3.60	<10	0.15	90	176	0.03	18	1210	46	<5	<20	34	0.01	<10	7	<10	<1	35
10	G37350	0.5	1.10	<5	50	<5	0.39	2	15	85	237	5.52	<10	0.35	128	63	0.03	8	1880	84	10	<20	29	0.02	<10	19	<10	<1	40
19	G37359	0.4	0.88	<5	50	<5	0.39	<1	12	77	329	3.75	<10	0.33	117	48	0.04	17	1860	34	5	<20	39	0.02	<10	17	<10	<1	39
Resplit:																													
1	G37341	0.8	0.59	<5	45	<5	0.27	2	14	119	657	3.86	<10	0.17	95	213	0.03	21	1270	50	<5	<20	35	0.02	<10	8	<10	<1	37
Standard:																													
Pb113		11.0	0.26	45	60	<5	1.65	38	2	5	2303	1.02	<10	0.11	1421	69	0.01	3	80	5450	20	<20	82	<0.01	<10	7	<10	<1	6981

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

JJ/nl
dl/5548S
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5553

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07079
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35216	0.76	0.022
2	G35217	0.47	0.014
3	G35218	0.95	0.028
4	G35219	<0.03	<0.001
5	G35220	0.37	0.011
6	G35221	0.53	0.015
7	G35222	0.37	0.011
8	G35223	0.67	0.020
9	G35224	0.61	0.018
10	G35225	1.78	0.052
11	G35226	0.46	0.013
12	G35227	1.11	0.032
13	G35228	1.45	0.042
14	G35229	1.08	0.031
15	G35230	2.85	0.083
16	G35231	0.84	0.024
17	G35232	0.43	0.013
18	G35233	0.47	0.014
19	G35234	0.50	0.015
20	G35235	1.88	0.055
21	G35236	1.77	0.052
22	G35237	6.40	0.187
23	G35238	1.43	0.042
24	G35239	0.98	0.029
25	G35240	1.31	0.038
26	G35241	0.58	0.017
27	G35242	1.72	0.050
28	G35243	0.67	0.020

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 17-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G35244	0.39	0.011
30	G35245	0.20	0.006
31	G35246	0.85	0.025
32	G35247	0.51	0.015
33	G35248	0.37	0.011
34	G35249	0.25	0.007
35	G35250	0.27	0.008

QC DATA:

Repeat:

1	G35216	0.80	0.023
4	G35219	<0.03	<0.001
10	G35225	1.91	0.056
13	G35228	1.45	0.042
15	G35230	3.10	0.090
19	G35234	0.32	0.009
21	G35236	1.42	0.041
22	G35237	6.04	0.176
27	G35242	1.67	0.049

Resplits:

1	G35216	0.88	0.026

Standard:

SI25		1.81	0.053

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

19-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5553

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07079
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35216	2.7	0.55	15	45	<5	0.64	2	6	160	2947	5.40	<10	0.40	446	12	0.01	2	580	20	<5	<20	46	<0.01	<10	55	<10	2	51
2	G35217	3.1	0.29	10	35	<5	0.67	2	9	181	3394	5.03	<10	0.24	469	12	0.01	2	340	28	<5	<20	36	<0.01	<10	27	<10	1	37
3	G35218	1.9	0.48	10	40	<5	0.64	2	8	173	2233	5.86	<10	0.36	620	42	0.01	2	490	20	<5	<20	40	<0.01	<10	37	<10	2	41
4	G35219	<0.2	1.09	10	270	<5	0.61	<1	7	132	8	2.29	<10	0.61	601	2	0.10	7	980	12	<5	<20	87	0.14	<10	44	<10	4	48
5	G35220	2.3	0.38	10	35	<5	0.50	2	7	169	1584	5.38	<10	0.32	443	12	0.01	2	450	58	<5	<20	31	<0.01	<10	27	<10	1	79
6	G35221	25.3	0.30	70	40	<5	1.21	7	10	183	3592	6.38	<10	0.49	833	24	0.01	2	440	66	30	<20	34	<0.01	<10	25	<10	2	330
7	G35222	2.2	0.24	5	30	<5	0.57	3	8	196	1634	5.20	<10	0.15	299	18	0.01	3	360	36	<5	<20	56	<0.01	<10	24	<10	<1	80
8	G35223	1.3	0.56	10	40	<5	0.51	2	5	187	1370	5.50	<10	0.43	458	14	0.01	2	510	14	<5	<20	41	<0.01	<10	70	<10	1	52
9	G35224	1.5	0.32	10	35	<5	0.37	2	6	232	1727	5.75	<10	0.19	267	16	0.01	3	320	14	<5	<20	41	<0.01	<10	63	<10	<1	28
10	G35225	1.6	0.36	10	40	<5	0.40	3	6	206	1561	7.55	<10	0.23	464	20	0.01	2	340	20	<5	<20	41	<0.01	<10	87	<10	<1	56
11	G35226	2.3	0.20	10	30	<5	0.22	3	8	295	2458	4.19	<10	0.16	332	11	0.01	6	150	34	<5	<20	13	<0.01	<10	35	<10	<1	84
12	G35227	2.3	0.26	10	35	<5	0.36	2	8	238	2292	6.21	<10	0.14	398	12	0.01	3	280	22	<5	<20	25	<0.01	<10	59	<10	<1	30
13	G35228	5.9	0.27	15	45	<5	0.47	30	17	200	5505	8.96	<10	0.23	484	20	0.01	2	380	96	<5	<20	23	<0.01	<10	53	<10	<1	1860
14	G35229	3.0	0.41	15	40	<5	0.67	2	7	172	2246	6.59	<10	0.24	534	106	0.01	1	470	48	5	<20	38	<0.01	<10	54	<10	2	73
15	G35230	4.1	0.63	20	45	<5	0.48	4	8	182	1998	9.35	<10	0.43	520	10	0.01	<1	430	218	<5	<20	16	<0.01	<10	148	<10	<1	178
16	G35231	4.4	0.28	10	30	<5	0.34	2	6	233	3020	5.05	<10	0.18	251	17	0.01	3	150	50	<5	<20	26	<0.01	<10	45	<10	<1	67
17	G35232	6.1	0.16	10	30	<5	0.24	2	8	255	3375	4.89	<10	0.12	209	16	0.01	4	100	54	<5	<20	9	<0.01	<10	36	<10	<1	48
18	G35233	9.5	0.09	15	45	<5	0.10	2	12	274	5768	5.31	<10	<0.01	68	16	0.01	4	130	32	10	<20	45	<0.01	<10	24	<10	<1	15
19	G35234	7.8	0.05	25	30	<5	0.12	2	9	268	2942	4.72	<10	<0.01	38	15	0.01	4	80	16	25	<20	18	<0.01	<10	25	<10	<1	17
20	G35235	4.0	0.96	40	50	<5	0.95	2	18	53	8611	4.12	20	0.57	204	546	0.03	61	490	52	20	<20	59	0.04	<10	36	<10	8	69
21	G35236	5.5	0.22	90	60	<5	1.15	2	7	238	1614	5.21	<10	0.47	699	21	0.01	3	210	14	10	<20	84	<0.01	<10	60	<10	1	28
22	G35237	10.5	0.20	245	60	<5	0.89	3	19	231	2295	8.36	<10	0.32	487	73	0.01	2	260	22	10	<20	56	<0.01	<10	54	<10	<1	31
23	G35238	5.7	0.18	105	65	<5	0.82	2	8	244	2991	5.47	<10	0.29	579	11	<0.01	3	260	20	<5	<20	72	<0.01	<10	48	<10	<1	24
24	G35239	5.3	0.15	60	40	<5	0.56	2	7	246	2533	5.29	<10	0.21	396	11	0.01	3	200	18	<5	<20	56	<0.01	<10	40	<10	<1	19
25	G35240	3.9	0.21	25	35	<5	0.42	2	7	321	2958	5.40	<10	0.14	274	18	0.01	6	170	16	<5	<20	39	<0.01	<10	45	<10	<1	23

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35241	7.2	0.15	10	30	<5	0.31	2	7	210	5987	4.89	<10	0.11	235	33	0.01	3	140	38	<5	<20	22	<0.01	<10	26	<10	<1	19
27	G35242	3.8	0.16	15	30	<5	0.34	2	4	308	3471	4.61	<10	0.10	232	15	0.01	6	130	10	<5	<20	13	<0.01	<10	43	<10	<1	18
28	G35243	3.5	0.12	5	30	<5	0.27	1	6	214	3495	4.76	<10	0.07	180	29	<0.01	3	120	12	<5	<20	16	<0.01	<10	47	<10	<1	9
29	G35244	2.3	0.09	10	30	<5	0.33	1	7	245	2070	3.99	<10	0.08	254	25	0.01	4	100	8	10	<20	32	<0.01	<10	39	<10	<1	10
30	G35245	1.1	0.13	5	25	5	0.12	1	6	245	621	4.36	<10	0.12	113	24	0.01	4	60	10	<5	<20	13	<0.01	<10	66	<10	<1	19
31	G35246	2.6	0.03	10	25	<5	0.04	2	12	264	2510	4.99	<10	<0.01	51	39	0.01	4	70	14	<5	<20	6	<0.01	<10	46	<10	<1	3
32	G35247	1.3	0.03	5	25	<5	0.05	1	5	282	1138	4.73	<10	<0.01	59	20	0.01	5	70	6	<5	<20	5	<0.01	<10	70	<10	<1	3
33	G35248	1.4	0.07	5	25	<5	0.12	1	5	288	1624	4.57	<10	0.05	96	19	0.01	5	70	8	<5	<20	25	<0.01	<10	83	<10	<1	13
34	G35249	1.0	0.04	5	30	10	0.06	2	12	241	714	6.13	<10	<0.01	47	39	0.01	3	90	10	<5	<20	9	<0.01	<10	46	<10	<1	3
35	G35250	1.7	0.05	5	25	<5	0.11	2	6	263	1971	4.76	<10	<0.01	74	23	0.01	4	90	8	<5	<20	7	<0.01	<10	50	<10	<1	8
QC DATA:																													
Repeat:																													
1	G35216	2.5	0.49	15	35	<5	0.59	2	6	156	2873	5.28	<10	0.39	439	12	0.01	2	560	20	<5	<20	44	<0.01	<10	53	<10	2	50
10	G35225	1.5	0.36	10	40	<5	0.40	3	6	198	1549	7.31	<10	0.22	456	20	0.01	2	330	20	<5	<20	38	<0.01	<10	84	<10	<1	54
19	G35234	7.7	0.05	25	25	<5	0.11	2	9	258	2898	4.55	<10	<0.01	35	14	0.01	4	70	14	25	<20	17	<0.01	<10	24	<10	<1	15
Resplit:																													
1	G35216	2.5	0.52	20	40	<5	0.47	2	6	138	2917	6.01	<10	0.41	357	14	0.01	1	620	22	<5	<20	37	<0.01	<10	78	<10	2	54
Standard:																													
Pb113		11.2	0.23	60	50	<5	1.62	38	2	<1	2316	1.03	<10	0.11	1474	60	0.01	1	80	5470	<5	<20	78	<0.01	<10	6	<10	1	7180

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5553
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5554

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07081
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37376	0.42	0.012
2	G37377	0.55	0.016
3	G37378	0.44	0.013
4	G37379	0.18	0.005
5	G37380	0.28	0.008
6	G37381	0.42	0.012
7	G37382	<0.03	<0.001
8	G37383	0.19	0.006
9	G37384	0.16	0.005
10	G37385	0.14	0.004
11	G37386	0.07	0.002
12	G37387	0.08	0.002
13	G37388	0.09	0.003
14	G37389	0.16	0.005
15	G37390	0.38	0.011
16	G37391	0.22	0.006
17	G37392	0.23	0.007
18	G37393	0.31	0.009
19	G37394	0.22	0.006
20	G37495	0.23	0.007
21	G37396	0.50	0.015
22	G37397	0.26	0.008
23	G37398	0.31	0.009
24	G37399	0.28	0.008
25	G37400	0.77	0.022
26	G37401	0.78	0.023
27	G37402	0.34	0.010

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5554 17-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G37403	0.30	0.009
29	G37404	1.01	0.029
30	G37405	0.45	0.013
31	G37406	0.84	0.024
32	G37407	0.26	0.008
33	G37408	<0.03	<0.001
34	G37409	0.51	0.015
35	G37410	0.57	0.017

QC DATA:

Repeat:

1	G37376	0.37	0.011
10	G37385	0.15	0.004
19	G37394	0.21	0.006
26	G37401	0.76	0.022
31	G37406	0.78	0.023

Resplits:

1	G37376	0.42	0.012

Standard:

SI25		1.80	0.052

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

19-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5554

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07081
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37376	0.3	0.44	<5	35	<5	0.49	1	17	78	290	5.46	<10	0.08	79	8	0.04	4	2200	20	<5	<20	23	0.02	<10	9	<10	2	49
2	G37377	0.2	0.41	<5	35	5	0.49	<1	19	82	220	5.92	<10	0.06	64	13	0.04	4	2220	18	<5	<20	18	0.03	<10	8	<10	1	37
3	G37378	0.3	0.43	<5	35	<5	0.46	2	17	122	282	5.65	<10	<0.01	29	11	0.05	4	2070	46	<5	<20	21	0.03	<10	8	<10	<1	47
4	G37379	0.2	0.30	<5	40	15	0.46	<1	19	82	84	5.91	<10	<0.01	24	6	0.04	4	2070	30	<5	<20	25	0.03	<10	6	<10	<1	16
5	G37380	0.4	0.42	<5	40	10	0.45	1	19	96	173	5.47	<10	0.01	34	5	0.05	4	2040	90	<5	<20	24	0.03	<10	8	<10	<1	63
6	G37381	0.2	0.33	<5	40	15	0.45	1	18	103	106	5.72	<10	<0.01	23	8	0.04	4	2000	42	<5	<20	26	0.03	<10	7	<10	<1	33
7	G37382	<0.2	1.08	5	275	<5	0.64	<1	8	94	5	2.19	<10	0.57	566	2	0.13	6	970	20	<5	<20	89	0.18	<10	46	<10	3	41
8	G37383	0.3	0.34	10	45	25	0.48	1	20	86	202	6.22	<10	<0.01	28	9	0.05	3	2160	28	<5	<20	24	0.03	<10	8	<10	<1	21
9	G37384	0.2	0.31	15	50	10	0.50	1	18	81	112	5.50	<10	<0.01	23	7	0.04	3	2260	38	<5	<20	33	0.03	<10	7	<10	1	14
10	G37385	0.3	0.27	15	40	10	0.36	1	16	83	104	4.20	<10	<0.01	16	9	0.04	23	1590	20	<5	<20	22	0.02	<10	4	<10	1	14
11	G37386	<0.2	0.17	<5	30	10	0.21	<1	11	80	18	3.14	<10	<0.01	12	6	0.03	16	950	8	<5	<20	19	0.02	<10	3	<10	<1	<1
12	G37387	<0.2	0.26	5	40	10	0.32	<1	13	81	50	3.67	<10	<0.01	16	7	0.03	21	1400	20	<5	<20	23	0.02	<10	4	<10	<1	9
13	G37388	<0.2	0.32	<5	40	25	0.39	<1	15	90	33	4.27	<10	<0.01	21	9	0.04	22	1760	28	<5	<20	25	0.02	<10	5	<10	1	7
14	G37389	0.2	0.36	15	40	35	0.47	1	19	103	99	5.13	<10	<0.01	21	16	0.05	11	2120	38	<5	<20	27	0.03	<10	7	<10	<1	16
15	G37390	0.4	0.31	50	40	15	0.66	2	18	75	204	5.59	<10	<0.01	347	7	0.04	4	2070	38	<5	<20	27	0.03	<10	10	<10	3	35
16	G37391	0.5	0.35	<5	45	<5	2.40	1	16	73	778	3.46	<10	0.71	684	44	0.02	6	1570	14	<5	<20	80	0.02	<10	13	<10	5	46
17	G37392	1.1	0.66	<5	50	<5	2.11	<1	14	82	924	3.14	<10	0.90	652	40	0.02	4	1530	16	<5	<20	65	0.02	<10	21	<10	4	47
18	G37393	0.9	0.97	<5	50	<5	1.77	1	16	83	814	3.69	<10	1.06	702	56	0.02	6	1530	20	<5	<20	118	0.03	<10	33	<10	6	60
19	G37394	0.8	2.16	20	95	<5	1.52	<1	22	67	731	4.96	<10	2.18	1009	31	0.02	7	1580	36	<5	<20	106	0.04	<10	71	<10	5	104
20	G37495	0.9	1.54	5	110	<5	2.25	<1	17	67	969	4.44	<10	1.26	877	31	0.03	5	1580	28	<5	<20	179	0.04	<10	52	<10	4	75
21	G37396	0.9	1.64	10	175	<5	2.03	1	16	67	1029	4.91	<10	1.42	818	43	0.04	4	1540	30	5	<20	197	0.04	<10	73	<10	5	73
22	G37397	1.0	1.53	<5	85	<5	1.80	1	17	91	978	4.48	<10	1.20	751	47	0.02	6	1620	32	10	<20	144	0.04	<10	51	<10	4	57
23	G37398	1.0	1.47	15	115	<5	0.94	1	16	81	968	4.32	<10	1.14	647	29	0.03	5	1600	32	<5	<20	82	0.03	<10	47	<10	4	73
24	G37399	1.1	1.45	<5	165	<5	0.66	<1	14	102	1161	4.40	<10	1.09	559	42	0.03	4	1430	28	<5	<20	81	0.03	<10	54	<10	2	66
25	G37400	4.4	1.79	5	125	<5	1.08	2	14	86	1516	4.23	<10	1.51	961	26	0.01	5	1470	68	5	<20	86	0.03	<10	40	<10	4	99

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37401	8.4	1.25	15	50	<5	2.50	15	14	85	1504	3.80	<10	1.02	1460	35	<0.01	4	1360	490	<5	<20	160	0.04	<10	25	<10	4	694
27	G37402	2.9	1.24	<5	95	<5	2.57	13	13	92	1325	3.97	<10	0.94	1225	30	0.02	3	1240	124	<5	<20	217	0.03	<10	37	<10	3	377
28	G37403	1.1	1.26	5	160	<5	2.79	1	12	95	1172	4.15	<10	0.91	1120	33	0.02	4	1230	34	<5	<20	252	0.04	<10	41	<10	4	82
29	G37404	3.9	1.07	55	65	<5	0.80	4	18	58	3321	4.00	20	0.48	288	212	0.03	12	340	130	40	<20	36	0.05	<10	43	<10	6	149
30	G37405	1.4	1.33	<5	165	<5	0.96	<1	12	104	1672	4.43	<10	1.06	557	28	0.05	3	1290	30	<5	<20	125	0.03	<10	75	<10	3	66
31	G37406	1.9	1.39	<5	90	<5	2.08	1	14	108	2109	4.29	<10	1.12	890	40	0.02	4	1140	32	<5	<20	173	0.03	<10	50	<10	6	55
32	G37407	0.7	2.52	<5	265	<5	4.12	1	24	110	1200	5.29	<10	2.68	1219	20	0.03	31	1120	38	<5	<20	428	0.06	<10	108	<10	5	61
33	G37408	<0.2	4.16	40	460	<5	6.44	<1	38	121	75	6.40	<10	4.92	1957	7	0.02	80	670	58	20	<20	562	0.06	<10	132	<10	7	69
34	G37409	1.5	1.98	<5	150	<5	2.27	<1	16	91	1379	4.76	<10	1.92	1079	33	0.01	16	1200	44	5	<20	186	0.04	<10	63	<10	3	71
35	G37410	1.5	1.51	<5	105	<5	1.66	<1	14	103	1789	5.10	<10	1.31	908	24	0.03	3	1210	26	<5	<20	156	0.04	<10	75	<10	2	56
QC DATA:																													
Repeat:																													
1	G37376	0.3	0.41	<5	35	<5	0.48	<1	17	75	289	5.36	<10	0.07	76	8	0.04	3	2180	22	<5	<20	23	0.03	<10	8	<10	2	46
10	G37385	0.3	0.26	20	35	5	0.37	<1	17	84	107	4.29	<10	<0.01	16	9	0.04	22	1610	18	<5	<20	22	0.02	<10	4	<10	<1	14
19	G37394	0.8	2.16	15	105	<5	1.53	1	23	66	749	4.97	<10	2.18	1020	30	0.02	7	1590	36	<5	<20	113	0.04	<10	70	<10	5	106
Resplit:																													
1	G37376	0.3	0.44	<5	45	<5	0.50	<1	17	78	305	5.28	<10	0.09	89	8	0.04	3	2200	22	<5	<20	23	0.03	<10	8	<10	2	50
Standard:																													
Pb113		11.0	0.24	45	50	<5	1.77	37	3	5	2322	1.11	<10	0.10	1443	77	0.02	2	70	5418	15	<20	86	0.01	<10	7	<10	<1	6920

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa/jl
df/5554
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5555

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

18-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07080
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	E192401	0.26	0.008		
2	E192402	0.18	0.005		
3	E192403	0.14	0.004		
4	E192404	0.11	0.003		
5	E192405	0.18	0.005		
6	E192406	0.18	0.005		
7	E192407	0.19	0.006		
8	E192408	<0.03	<0.001		
9	E192409	0.38	0.011		
10	E192410	0.11	0.003		
11	E192411	0.24	0.007		
12	E192412	0.18	0.005		
13	E192413	0.21	0.006		
14	E192414	0.26	0.008		
15	E192415	0.19	0.006		
16	E192416	0.14	0.004		
17	E192417	0.23	0.007		
18	E192418	0.22	0.006		
19	E192419	0.35	0.010	53.6	1.563
20	E192420	0.48	0.014		
21	E192421	0.18	0.005		
22	E192422	0.32	0.009		
23	E192423	0.31	0.009		
24	E192424	0.29	0.008		
25	E192425	0.25	0.007		
26	E192426	0.30	0.009		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5555 18-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
27	E192427	0.21	0.006		
28	E192428	0.69	0.020		
29	E192429	0.44	0.013		
30	E192430	0.24	0.007		
31	E192431	0.23	0.007		
32	E192432	0.29	0.008		
33	E192433	0.18	0.005		
34	E192434	0.21	0.006		
35	E192435	0.24	0.007		
QC DATA:					
Repeat:					
1	E192401	0.25	0.007		
10	E192410	0.11	0.003		
19	E192419	0.35	0.010	52.9	1.543
28	E192428	0.73	0.021		
Resplits:					
1	E192401	0.24	0.007		
Standard:					
SI25		1.82	0.053		

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

19-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5555

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07080
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	E192401	0.9	1.28	15	125	<5	0.71	<1	17	60	1187	3.80	<10	0.98	701	18	0.03	7	1660	30	<5	<20	34	0.03	<10	53	<10	7	75
2	E192402	0.9	1.36	5	150	<5	1.07	<1	15	60	907	3.89	<10	1.01	601	31	0.03	4	1740	24	<5	<20	75	0.03	<10	50	<10	6	67
3	E192403	1.0	1.19	<5	85	<5	2.46	<1	17	60	810	3.89	<10	0.84	751	23	0.04	4	1820	28	<5	<20	171	0.03	<10	54	<10	6	69
4	E192404	0.8	1.21	<5	80	<5	3.35	<1	15	56	678	3.59	<10	0.88	992	17	0.03	3	1630	28	<5	<20	221	0.03	<10	43	<10	4	71
5	E192405	0.8	1.34	<5	80	<5	2.40	1	16	63	638	3.92	<10	1.02	777	27	0.03	4	1610	22	<5	<20	168	0.03	<10	50	<10	4	60
6	E192406	1.0	1.25	<5	75	<5	2.84	<1	18	57	679	3.76	<10	0.91	904	22	0.02	3	1570	24	<5	<20	190	0.04	<10	40	<10	4	58
7	E192407	0.9	1.27	<5	115	<5	3.03	<1	13	58	699	3.86	<10	0.95	869	48	0.03	3	1520	24	<5	<20	233	0.04	<10	48	<10	4	59
8	E192408	<0.2	1.05	<5	280	20	0.67	<1	8	110	8	2.19	<10	0.60	581	3	0.10	7	930	16	5	<20	81	0.15	<10	47	<10	4	43
9	E192409	1.3	1.31	<5	75	<5	2.15	<1	15	71	1046	3.49	<10	1.09	777	31	0.03	5	1520	24	<5	<20	163	0.03	<10	47	<10	6	66
10	E192410	0.7	1.26	<5	120	<5	2.82	<1	14	58	525	3.81	<10	0.95	849	39	0.03	3	1620	22	<5	<20	220	0.04	<10	47	<10	4	59
11	E192411	1.0	1.32	<5	100	<5	2.49	<1	16	91	764	3.59	<10	0.99	772	42	0.04	4	1590	22	<5	<20	231	0.03	<10	49	<10	4	56
12	E192412	1.1	1.06	<5	105	<5	2.08	<1	13	75	739	3.30	<10	0.76	683	31	0.03	5	1540	20	<5	<20	260	0.03	<10	43	<10	5	47
13	E192413	0.9	1.30	<5	70	<5	3.07	1	16	72	672	4.59	<10	0.88	895	34	0.05	4	1930	22	<5	<20	286	0.04	<10	66	<10	4	63
14	E192414	1.3	1.24	<5	95	<5	2.69	1	17	60	824	4.10	<10	0.92	773	36	0.04	5	1660	24	<5	<20	222	0.04	<10	60	<10	4	53
15	E192415	1.0	1.11	<5	120	<5	2.44	<1	15	66	647	3.70	<10	0.78	680	37	0.05	4	1540	20	<5	<20	210	0.04	<10	56	<10	4	45
16	E192416	1.3	1.26	<5	120	<5	2.90	<1	10	73	829	3.64	<10	0.99	804	54	0.04	3	1350	20	<5	<20	235	0.03	<10	59	<10	4	49
17	E192417	1.2	1.27	5	130	<5	2.56	<1	17	70	783	4.48	<10	0.98	825	46	0.05	4	1590	40	<5	<20	218	0.04	<10	65	<10	6	66
18	E192418	1.6	1.34	<5	130	<5	1.87	<1	15	94	729	3.97	<10	1.03	661	39	0.04	4	1450	22	<5	<20	177	0.03	<10	58	<10	2	55
19	E192419	>30	1.09	20	65	<5	5.78	41	12	70	2004	3.42	<10	0.92	2088	36	0.02	4	1150	1456	15	<20	339	0.04	<10	39	<10	7	2133
20	E192420	23.4	1.11	30	35	<5	2.92	57	16	58	2923	3.69	<10	0.90	1181	48	0.01	3	1360	984	15	<20	172	0.03	<10	33	<10	3	3100
21	E192421	1.1	1.47	15	75	<5	3.07	1	15	51	646	3.56	<10	1.19	968	44	0.02	5	1660	42	10	<20	192	0.03	<10	45	<10	7	89
22	E192422	3.3	1.19	10	65	<5	2.68	2	16	81	1337	3.37	<10	0.88	907	44	<0.01	6	1550	36	10	<20	110	0.03	<10	31	<10	8	91
23	E192423	6.3	1.28	35	75	<5	2.18	9	15	78	1385	3.44	<10	1.00	980	35	<0.01	6	1540	366	20	<20	145	0.03	<10	35	<10	8	533
24	E192424	1.7	1.25	20	95	<5	2.11	<1	18	67	1083	3.81	<10	0.83	727	45	0.02	2	1540	34	<5	<20	173	0.04	<10	44	<10	7	91
25	E192425	1.0	1.18	15	115	<5	2.99	<1	15	68	946	3.07	<10	0.84	894	72	0.02	5	1620	32	5	<20	201	0.03	<10	33	<10	8	69

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	E192426	1.8	1.25	30	65	<5	1.46	2	18	55	1310	3.63	<10	0.93	751	45	0.01	7	1630	30	15	<20	78	0.02	<10	34	<10	9	89
27	E192427	1.1	1.26	30	145	<5	0.88	<1	16	61	861	3.51	<10	0.90	562	25	0.02	4	1720	32	<5	<20	64	0.03	<10	38	<10	8	78
28	E192428	2.4	1.14	30	65	<5	1.34	1	15	76	2069	3.80	<10	0.83	661	96	0.02	4	1390	60	<5	<20	81	0.03	<10	39	<10	7	91
29	E192429	1.3	1.26	<5	75	<5	1.55	3	15	59	1301	3.96	<10	0.99	539	60	0.04	8	1440	18	25	<20	125	0.01	<10	54	<10	5	52
30	E192430	0.9	1.35	<5	100	<5	1.66	1	18	56	993	4.73	<10	1.01	581	33	0.04	6	1510	22	10	<20	176	0.03	<10	66	<10	5	61
31	E192431	0.9	1.28	<5	100	<5	2.25	1	15	63	878	3.87	<10	1.02	700	68	0.04	6	1450	24	10	<20	221	0.03	<10	59	<10	6	56
32	E192432	3.0	1.06	20	50	<5	1.01	3	22	54	2604	3.63	10	0.57	194	182	0.03	9	450	60	10	<20	61	0.05	<10	43	<10	6	268
33	E192433	0.7	1.28	<5	115	<5	1.92	1	15	57	808	3.92	<10	1.02	573	35	0.04	5	1490	22	5	<20	168	0.03	<10	51	<10	5	57
34	E192434	0.9	1.24	<5	135	<5	1.90	1	14	60	863	3.63	<10	0.95	584	31	0.03	4	1520	24	10	<20	153	0.03	<10	41	<10	5	59
35	E192435	0.8	1.22	<5	90	<5	2.64	<1	17	59	875	3.61	<10	0.96	768	45	0.01	5	1480	24	10	<20	171	0.03	<10	34	<10	6	53
QC DATA:																													
Repeat:																													
1	E192401	1.0	1.28	10	135	<5	0.72	<1	17	59	1196	3.78	<10	0.98	703	18	0.03	7	1650	28	<5	<20	33	0.03	<10	52	<10	8	72
10	E192410	0.8	1.30	<5	125	<5	2.87	<1	14	58	543	3.89	<10	0.98	866	39	0.03	3	1660	24	<5	<20	225	0.04	<10	49	<10	5	60
19	E192419	>30	1.10	20	50	<5	5.80	40	10	69	2013	3.45	<10	0.91	2094	32	0.02	<1	1110	1466	<5	<20	335	0.05	<10	39	<10	4	2154
Resplit:																													
1	E192401	1.0	1.25	5	115	<5	0.77	1	16	62	1133	3.85	<10	0.97	655	20	0.03	9	1610	28	5	<20	31	0.03	<10	53	<10	8	70
Standard:																													
Pb113		11.0.	0.24	45	50	<5	1.77	37	3	5	2322	1.11	<10	0.10	1443	77	0.02	2	70	5418	25	<20	79	0.01	<10	7	<10	<1	6920

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa/jl
df/5554
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5560

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07082
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	E192436	0.41	0.012
2	E192437	0.25	0.007
3	E192438	0.39	0.011
4	E192439	0.23	0.007
5	E192440	0.34	0.010
6	E192441	1.01	0.029
7	E192442	0.32	0.009
8	E192443	0.30	0.009
9	E192444	0.35	0.010
10	E192445	0.32	0.009
11	E192446	0.30	0.009
12	E192447	0.44	0.013
13	E192448	0.37	0.011
14	E192449	0.43	0.013
15	E192450	0.50	0.015
16	E192451	0.32	0.009
17	E192452	0.38	0.011
18	E192453	0.33	0.010
19	E192454	0.32	0.009
20	E192455	0.30	0.009
21	E192456	0.29	0.008
22	E192457	0.20	0.006
23	E192458	0.16	0.005
24	E192459	0.21	0.006
25	E192460	<0.03	<0.001
26	E192461	0.29	0.008
27	E192462	0.25	0.007
28	E192463	0.29	0.008

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5560 17-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	E192464	0.21	0.006
30	E192465	0.12	0.003
31	E192466	1.09	0.032
32	E192467	<0.03	<0.001
33	E192468	0.24	0.007
34	E192469	0.39	0.011
35	E192470	0.54	0.016

QC DATA:

Repeat:

1	E192436	0.42	0.012
10	E192445	0.30	0.009
19	E192454	0.31	0.009
31	E192466	0.98	0.029

Resplits:

1	E192436	0.41	0.012

Standard:

SI25		1.81	0.053

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

19-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5560

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07082
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	E192436	1.1	1.33	<5	125	<5	2.53	1	11	64	1245	3.10	<10	1.05	741	60	0.02	5	1470	22	10	<20	171	0.02	<10	37	<10	4	54
2	E192437	0.8	1.36	<5	185	<5	2.08	<1	11	72	810	3.22	<10	1.12	655	73	0.02	4	1450	26	<5	<20	183	0.02	<10	40	<10	5	55
3	E192438	0.8	0.62	<5	95	<5	1.70	<1	6	43	766	1.55	<10	0.52	470	32	<0.01	3	820	16	5	<20	121	<0.01	<10	14	<10	3	33
4	E192439	0.5	0.52	5	120	<5	2.64	<1	5	33	549	1.51	<10	0.38	627	24	<0.01	2	930	16	<5	<20	202	0.01	<10	13	<10	2	26
5	E192440	0.8	1.28	15	145	<5	2.84	<1	10	65	1050	3.16	<10	0.95	757	32	0.02	5	1520	26	10	<20	219	0.02	<10	35	<10	4	57
6	E192441	3.6	1.12	60	75	<5	0.73	3	16	59	3292	3.90	20	0.52	271	220	0.03	13	410	134	35	<20	32	0.04	<10	43	<10	5	154
7	E192442	0.9	1.13	5	135	<5	1.92	1	11	58	1035	2.80	<10	0.87	605	46	0.01	4	1430	24	10	<20	166	0.02	<10	27	<10	5	54
8	E192443	0.8	1.12	10	155	<5	2.35	<1	9	88	945	2.54	<10	0.88	730	35	0.02	4	1250	22	5	<20	251	0.02	<10	29	<10	4	52
9	E192444	1.2	1.38	10	145	<5	2.22	<1	12	60	1163	3.58	<10	1.04	804	42	0.03	6	1510	28	5	<20	245	0.02	<10	37	<10	5	61
10	E192445	0.9	1.41	10	90	<5	2.00	<1	12	75	869	3.20	<10	1.23	839	44	0.02	5	1440	28	10	<20	173	0.02	<10	40	<10	4	66
11	E192446	1.0	1.70	10	210	<5	1.43	1	11	68	1201	3.91	<10	1.58	738	32	0.04	7	1480	28	20	<20	160	0.02	<10	67	<10	3	64
12	E192447	1.3	1.65	<5	160	<5	1.17	<1	10	86	1621	4.30	<10	1.56	710	37	0.03	5	1270	30	5	<20	148	0.03	<10	66	<10	3	62
13	E192448	0.9	1.83	10	265	<5	1.48	<1	11	88	1118	4.57	<10	1.73	849	32	0.04	5	1490	30	10	<20	191	0.03	<10	85	<10	4	66
14	E192449	1.4	1.66	10	135	<5	1.37	<1	10	107	1564	3.58	<10	1.59	774	54	0.03	6	1340	32	10	<20	152	0.02	<10	62	<10	4	58
15	E192450	1.7	1.33	10	125	<5	1.77	<1	9	128	1963	3.05	<10	1.34	876	51	0.02	7	1010	28	10	<20	186	0.02	<10	44	<10	4	51
16	E192451	1.3	1.72	10	230	<5	2.48	<1	10	69	1176	3.60	<10	1.56	1087	48	0.03	6	1530	30	10	<20	275	0.03	<10	56	<10	5	69
17	E192452	1.1	1.63	10	105	<5	2.61	<1	14	78	1233	3.64	<10	1.47	1139	47	0.02	5	1510	34	10	<20	235	0.03	<10	49	<10	6	65
18	E192453	1.0	1.59	5	240	<5	2.33	1	13	58	1136	4.29	<10	1.36	980	37	0.03	4	1590	28	5	<20	211	0.03	<10	61	<10	4	76
19	E192454	0.8	1.37	5	210	<5	2.54	<1	11	78	979	3.66	<10	1.12	786	115	0.03	5	1380	24	<5	<20	253	0.03	<10	54	<10	3	61
20	E192455	0.9	1.37	5	140	<5	2.31	<1	12	68	1116	3.60	<10	1.14	753	123	0.04	5	1500	28	10	<20	213	0.02	<10	55	<10	4	66
21	E192456	1.2	1.37	5	155	<5	1.81	<1	14	55	1162	4.12	<10	1.10	623	56	0.04	5	1560	26	5	<20	161	0.02	<10	62	<10	3	70
22	E192457	0.7	1.41	10	125	<5	2.37	1	12	70	772	3.61	<10	1.19	862	90	0.03	7	1570	28	20	<20	198	0.02	<10	57	<10	4	88
23	E192458	0.6	1.39	5	235	<5	2.35	<1	10	74	557	3.63	<10	1.11	787	82	0.03	5	1530	26	5	<20	202	0.03	<10	52	<10	4	71
24	E192459	1.4	1.26	15	110	<5	2.73	3	10	78	915	3.12	<10	0.96	1002	133	0.02	5	1510	202	5	<20	208	0.03	<10	49	<10	5	201
25	E192460	<0.2	1.15	15	265	15	0.67	<1	6	82	5	2.23	<10	0.60	552	4	0.15	8	940	24	5	<20	96	0.14	<10	45	<10	5	43

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	E192461	1.6	1.29	10	115	<5	2.16	5	11	58	1121	3.26	<10	0.97	904	51	0.02	5	1580	132	10	<20	165	0.02	<10	53	<10	6	320
27	E192462	1.4	1.39	15	100	<5	1.21	<1	16	63	963	4.15	<10	1.04	663	62	0.02	5	1710	52	5	<20	101	0.02	<10	65	<10	4	111
28	E192463	1.7	1.38	10	120	<5	2.47	<1	14	63	936	4.07	<10	1.09	928	73	0.03	5	1530	32	5	<20	220	0.03	<10	71	<10	4	68
29	E192464	1.6	1.46	5	80	<5	1.51	<1	14	72	802	3.94	<10	1.25	827	58	0.02	6	1460	60	10	<20	109	0.04	<10	55	<10	3	79
30	E192465	1.0	2.84	15	240	<5	3.69	1	29	135	618	5.15	<10	3.08	1429	24	0.03	60	1020	102	10	<20	273	0.13	<10	111	<10	5	112
31	E192466	3.6	3.25	30	270	<5	8.69	13	35	151	1234	5.24	<10	3.58	2338	7	0.01	104	390	578	20	<20	454	0.14	<10	86	<10	5	617
32	E192467	<0.2	4.09	30	1075	25	5.48	<1	36	199	75	5.51	<10	5.14	1663	5	0.02	122	510	66	20	<20	393	0.23	<10	115	<10	7	73
33	E192468	3.8	1.27	25	145	<5	2.37	1	12	77	1201	3.46	<10	0.95	841	32	0.02	7	1470	34	15	<20	144	0.05	<10	39	<10	4	87
34	E192469	3.9	1.03	15	80	<5	3.14	1	12	96	1189	2.81	<10	0.74	1027	32	<0.01	6	1330	40	10	<20	134	0.04	<10	26	<10	5	83
35	E192470	2.6	1.18	10	75	<5	2.19	<1	11	119	1385	3.56	<10	0.89	774	36	<0.01	5	1290	68	10	<20	119	0.05	<10	35	<10	4	67
QC DATA:																													
Repeat:																													
1	E192436	1.0	1.39	10	160	<5	2.50	<1	11	66	1231	3.09	<10	1.04	734	59	0.02	4	1500	26	5	<20	170	0.02	<10	39	<10	5	54
10	E192445	1.0	1.45	5	80	<5	2.08	<1	12	79	890	3.32	<10	1.26	872	51	0.02	6	1520	32	10	<20	179	0.02	<10	41	<10	4	70
19	E192454	0.9	1.34	10	205	<5	2.48	<1	10	79	949	3.59	<10	1.09	766	105	0.03	4	1370	26	5	<20	250	0.03	<10	54	<10	4	61
Resplit:																													
1	E192436	1.1	1.34	15	150	<5	2.44	<1	12	62	1185	3.14	<10	1.02	715	55	0.02	4	1590	30	10	<20	168	0.02	<10	38	<10	5	56
Standard:																													
Pb113		11.3	0.26	60	60	<5	1.71	39	1	6	2279	1.06	<10	0.10	1456	83	0.02	2	90	5516	20	<20	73	0.02	<10	6	<10	<1	6914

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

JJ/jl
df/5560
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

1004 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5561

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07086
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	E192506	0.35	0.010
2	E192507	0.50	0.015
3	E192508	0.20	0.006
4	E192509	0.37	0.011
5	E192510	0.48	0.014
6	E192511	0.42	0.012
7	E192512	0.42	0.012
8	E192513	0.22	0.006
9	E192514	0.33	0.010
10	E192515	0.23	0.007
11	E192516	0.70	0.020
12	E192517	0.27	0.008
13	E192518	0.52	0.015
14	E192519	0.75	0.022
15	E192520	0.30	0.009
16	E192521	0.45	0.013
17	E192522	0.43	0.013
18	E192523	0.33	0.010
19	E192524	0.45	0.013
20	E192525	0.30	0.009
21	E192526	0.37	0.011
22	E192527	0.32	0.009
23	E192528	<0.03	<0.001
24	E192529	0.38	0.011
25	E192530	0.29	0.008
26	E192531	0.37	0.011
27	E192532	0.15	0.004

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5561 17-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	E192533	0.33	0.010
29	E192534	0.17	0.005
30	E192535	0.16	0.005
31	E192536	0.25	0.007
32	E192537	0.20	0.006
33	E192538	0.48	0.014
34	E192539	0.49	0.014
35	E192540	0.34	0.010

QC DATA:

Repeat:

1	E192506	0.34	0.010
10	E192515	0.25	0.007
19	E192524	0.43	0.013

Resplits:

1	E192506	0.35	0.010

Standard:

SI25		1.69	0.049

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

19-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5561

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07086
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	E192506	1.4	1.13	10	200	<5	2.32	<1	11	94	1499	3.77	<10	0.87	897	36	0.04	7	1320	30	10	<20	154	0.07	<10	69	<10	4	100
2	E192507	2.1	0.79	10	155	<5	2.17	<1	8	111	2050	2.87	<10	0.54	729	19	0.03	5	1020	24	<5	<20	196	0.06	<10	49	<10	3	73
3	E192508	0.9	0.84	10	320	<5	3.37	<1	7	97	834	2.84	<10	0.56	960	17	0.03	5	1030	134	10	<20	208	0.07	<10	37	<10	6	73
4	E192509	1.4	0.75	15	195	<5	1.09	<1	9	110	1572	3.14	<10	0.50	446	47	0.05	6	1270	24	<5	<20	71	0.06	<10	60	<10	3	69
5	E192510	1.1	0.81	5	205	<5	2.12	1	10	90	1576	3.51	<10	0.52	719	49	0.03	5	1310	42	<5	<20	132	0.06	<10	49	<10	4	102
6	E192511	1.1	1.08	15	280	<5	1.84	<1	10	92	1474	3.55	<10	0.87	731	102	0.04	5	1190	36	10	<20	147	0.07	<10	63	<10	4	94
7	E192512	1.6	1.18	15	170	<5	1.81	1	11	91	1925	3.54	<10	0.95	763	75	0.03	5	1350	38	<5	<20	133	0.05	<10	52	<10	4	106
8	E192513	0.8	1.08	15	170	<5	2.88	1	11	72	1062	3.67	<10	0.70	1009	42	0.02	7	1460	30	15	<20	158	0.05	<10	53	<10	5	86
9	E192514	1.2	0.98	20	290	<5	2.67	<1	10	64	1705	3.65	<10	0.71	865	129	0.05	4	1530	24	5	<20	219	0.07	<10	69	<10	5	88
10	E192515	1.1	0.93	10	185	<5	1.36	1	8	104	1323	3.12	<10	0.71	638	43	0.04	5	1070	28	10	<20	134	0.06	<10	60	<10	3	104
11	E192516	1.0	0.89	15	285	<5	2.25	<1	9	102	1043	3.61	<10	0.66	814	50	0.05	6	1220	34	<5	<20	182	0.08	<10	79	<10	4	98
12	E192517	0.8	1.03	10	355	<5	2.43	<1	8	102	1172	3.21	<10	0.80	953	79	0.05	6	1250	32	10	<20	188	0.08	<10	71	<10	5	108
13	E192518	2.2	0.81	20	95	<5	2.00	1	9	133	2112	2.87	<10	0.62	756	94	0.03	6	750	32	5	<20	157	0.05	<10	54	<10	2	90
14	E192519	2.8	1.00	20	150	<5	1.43	1	11	131	3567	3.46	<10	0.77	657	154	0.05	6	890	28	5	<20	103	0.07	<10	81	<10	3	98
15	E192520	1.1	1.19	10	205	<5	3.14	<1	11	98	1122	4.13	<10	0.91	1191	73	0.03	6	1500	32	5	<20	212	0.07	<10	70	<10	3	106
16	E192521	1.3	1.16	10	200	<5	1.52	1	12	92	1692	4.31	<10	0.92	768	107	0.05	6	1350	28	<5	<20	116	0.08	<10	87	<10	3	117
17	E192522	1.6	0.95	5	175	<5	1.94	1	11	97	1400	4.00	<10	0.74	743	103	0.05	5	1260	24	<5	<20	166	0.08	<10	81	<10	4	89
18	E192523	0.9	0.87	15	350	<5	2.79	<1	9	81	1121	3.73	<10	0.57	882	80	0.04	5	1390	24	<5	<20	237	0.07	<10	66	<10	4	80
19	E192524	1.9	1.03	15	155	<5	1.62	1	12	112	1929	3.42	<10	0.72	708	77	0.03	6	1320	36	5	<20	88	0.06	<10	46	<10	4	93
20	E192525	1.8	1.08	20	85	<5	2.03	3	11	71	1818	3.82	<10	0.82	845	71	0.03	5	1450	110	<5	<20	91	0.07	<10	62	<10	4	207
21	E192526	2.8	1.15	35	95	<5	3.07	3	9	94	1510	2.65	<10	0.84	1537	59	<0.01	6	1520	78	10	<20	90	0.06	<10	24	<10	5	200
22	E192527	1.6	1.05	30	130	<5	2.35	<1	10	103	973	2.43	<10	0.62	1035	75	<0.01	5	1460	32	10	<20	96	0.05	<10	18	<10	5	78
23	E192528	<0.2	1.09	20	275	20	0.63	<1	6	108	5	2.33	<10	0.61	567	2	0.11	7	930	16	<5	<20	95	0.14	<10	47	<10	2	48
24	E192529	3.4	1.10	45	90	<5	3.27	1	11	81	1217	3.21	<10	0.73	1384	64	0.01	5	1450	54	10	<20	101	0.06	<10	23	<10	5	121
25	E192530	4.6	0.90	30	70	<5	3.23	<1	11	81	1154	3.59	<10	0.51	1191	74	0.01	5	1560	62	<5	<20	88	0.05	<10	24	<10	4	108

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	E192531	2.8	1.09	25	90	<5	3.27	1	10	70	1356	3.05	<10	0.66	1282	65	<0.01	5	1540	36	10	<20	135	0.06	<10	22	<10	5	117
27	E192532	0.6	0.71	15	120	<5	4.02	<1	7	75	514	2.33	<10	0.37	797	39	0.01	4	1270	22	<5	<20	264	0.06	<10	23	<10	6	44
28	E192533	4.8	1.29	45	70	<5	1.12	3	23	66	2684	3.78	20	0.69	216	227	0.04	10	480	70	10	<20	56	0.06	<10	51	<10	5	301
29	E192534	0.9	0.73	20	130	<5	3.32	<1	8	88	798	2.20	<10	0.43	739	35	<0.01	5	1120	28	10	<20	166	0.05	<10	19	<10	6	50
30	E192535	0.6	0.87	25	110	<5	3.78	<1	8	87	799	2.16	<10	0.53	984	36	<0.01	4	1230	22	10	<20	169	0.06	<10	15	<10	6	57
31	E192536	1.3	0.87	30	90	<5	3.30	<1	7	83	1287	2.77	<10	0.52	973	235	0.01	3	1140	48	5	<20	92	0.05	<10	14	<10	4	68
32	E192537	0.5	0.79	20	110	<5	3.97	<1	8	77	855	2.86	<10	0.44	850	48	0.02	3	1220	36	<5	<20	233	0.07	<10	29	<10	5	59
33	E192538	1.4	0.67	25	95	<5	2.93	1	7	110	2003	2.02	<10	0.40	661	50	0.01	4	910	32	5	<20	169	0.05	<10	16	<10	4	57
34	E192539	1.6	0.97	25	90	<5	1.52	<1	9	105	2248	2.38	<10	0.70	701	172	0.01	3	990	28	5	<20	70	0.06	<10	20	<10	6	68
35	E192540	1.1	0.79	30	100	<5	2.93	<1	9	121	1326	1.93	<10	0.48	692	271	0.02	4	1040	38	5	<20	179	0.06	<10	16	<10	5	47
QC DATA:																													
Repeat:																													
1	E192506	1.4	1.10	15	215	<5	2.33	<1	11	94	1526	3.78	<10	0.88	905	36	0.04	5	1340	30	5	<20	162	0.06	<10	68	<10	4	98
10	E192515	1.1	0.92	15	180	<5	1.39	2	8	107	1326	3.16	<10	0.71	647	44	0.04	6	1090	30	10	<20	133	0.06	<10	60	<10	3	107
19	E192524	1.7	1.08	25	150	<5	1.70	<1	13	119	2009	3.57	<10	0.75	744	83	0.03	6	1420	38	<5	<20	87	0.06	<10	48	<10	4	97
Resplit:																													
1	E192506	1.6	1.16	15	215	<5	2.23	<1	12	77	1617	4.22	<10	0.91	883	39	0.04	6	1490	34	5	<20	152	0.08	<10	77	<10	4	108
Standard:																													
Pb113		11.8	0.26	70	60	<5	1.71	39	1	6	2234	1.06	<10	0.10	1452	84	0.02	2	90	5546	20	<20	82	0.02	<10	7	<10	<1	7102

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

JJ/jl
df/5560
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

1004 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5562

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

18-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07083
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	E192471	0.37	0.011
2	E192472	0.14	0.004
3	E192473	0.21	0.006
4	E192474	0.25	0.007
5	E192475	0.28	0.008
6	E192476	0.29	0.008
7	E192477	0.21	0.006
8	E192478	0.40	0.012
9	E192479	0.38	0.011
10	E192480	0.59	0.017
11	E192481	1.80	0.052
12	E192482	0.76	0.022
13	E192483	0.44	0.013
14	E192484	0.39	0.011
15	E192485	0.43	0.013
16	E192486	0.49	0.014
17	E192487	1.09	0.032
18	E192488	0.75	0.022
19	E192489	0.47	0.014
20	E192490	0.34	0.010
21	E192491	0.36	0.010
22	E192492	<0.03	<0.001
23	E192493	0.58	0.017
24	E192494	0.36	0.010
25	E192495	0.29	0.008
26	E192496	0.29	0.008
27	E192497	0.40	0.012
28	E192498	0.61	0.018

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5562 18-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	E192499	0.46	0.013
30	E192500	0.30	0.009
31	E192501	0.26	0.008
32	E192502	0.17	0.005
33	E192503	0.33	0.010
34	E192504	0.40	0.012
35	E192505	0.58	0.017

QC DATA:

Repeat:

1	E192471	0.39	0.011
10	E192480	0.65	0.019
19	E192489	0.47	0.014

Resplits:

1	E192471	0.38	0.011

Standard:

SI25		1.83	0.053

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO-TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

19-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5562

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07083
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	E192471	2.2	1.40	20	130	<5	1.76	<1	13	70	1387	3.89	<10	1.04	760	51	0.02	5	1450	42	<5	<20	103	0.05	<10	50	<10	5	70
2	E192472	0.8	1.18	30	100	<5	3.55	<1	11	78	486	3.26	<10	0.81	1056	25	0.01	4	1360	44	<5	<20	190	0.05	<10	31	<10	6	86
3	E192473	1.2	1.31	25	115	<5	3.52	<1	11	73	765	3.76	<10	0.95	1097	29	0.01	4	1310	36	<5	<20	147	0.05	<10	41	<10	5	80
4	E192474	1.7	1.38	20	105	<5	3.15	<1	13	75	972	3.57	<10	1.03	1012	44	0.02	7	1480	32	10	<20	160	0.05	<10	42	<10	4	73
5	E192475	1.4	1.38	25	125	<5	2.17	<1	14	78	984	3.33	<10	1.10	776	42	0.02	5	1500	32	10	<20	174	0.04	<10	43	<10	5	70
6	E192476	1.6	1.35	20	205	<5	2.45	1	12	90	1235	3.33	<10	1.01	799	76	0.03	5	1430	42	<5	<20	170	0.06	<10	47	<10	7	65
7	E192477	1.1	1.19	25	145	<5	2.74	<1	12	68	700	3.47	<10	0.78	790	38	0.03	4	1620	30	<5	<20	187	0.05	<10	38	<10	6	52
8	E192478	1.4	1.30	15	190	<5	2.21	<1	13	74	1072	3.61	<10	0.90	766	45	0.03	3	1620	36	<5	<20	140	0.04	<10	42	<10	6	60
9	E192479	1.6	1.38	30	100	<5	1.94	<1	15	75	1223	3.64	<10	0.98	776	44	0.02	5	1560	46	10	<20	114	0.04	<10	35	<10	6	74
10	E192480	2.3	1.26	20	90	<5	2.77	<1	17	88	2068	3.63	<10	0.87	1016	54	<0.01	5	1290	34	10	<20	134	0.03	<10	30	<10	5	62
11	E192481	4.0	1.16	50	70	<5	1.13	3	25	60	8577	4.60	20	0.62	218	625	0.04	65	220	78	25	<20	61	0.05	<10	46	<10	6	80
12	E192482	3.2	1.21	25	80	<5	2.93	<1	13	92	2709	3.63	<10	0.80	1016	48	<0.01	5	1310	40	10	<20	153	0.02	<10	34	<10	5	72
13	E192483	2.2	1.11	40	95	<5	3.53	<1	11	118	1910	2.90	<10	0.76	1146	36	<0.01	4	1140	42	<5	<20	146	0.03	<10	26	<10	6	69
14	E192484	1.7	1.15	25	180	<5	4.00	<1	12	87	1529	3.39	<10	0.64	1198	40	<0.01	5	1560	32	<5	<20	215	0.04	<10	30	<10	7	64
15	E192485	1.5	1.04	25	80	<5	2.86	7	11	103	1087	3.00	<10	0.64	883	30	<0.01	6	1380	54	10	<20	140	0.02	<10	22	<10	4	297
16	E192486	1.9	1.04	25	105	<5	2.92	<1	10	126	1344	2.85	<10	0.67	966	46	<0.01	5	1130	78	5	<20	160	0.04	<10	23	<10	5	69
17	E192487	2.1	0.96	30	65	<5	3.69	1	12	147	1263	3.13	<10	0.62	990	31	<0.01	6	1100	106	<5	<20	156	0.03	<10	25	<10	4	75
18	E192488	2.9	1.15	30	70	<5	1.71	<1	12	122	2142	3.22	<10	0.84	734	38	<0.01	6	1060	40	10	<20	102	0.02	<10	31	<10	5	76
19	E192489	2.2	1.33	40	120	<5	2.29	<1	13	91	1701	3.38	<10	0.97	929	33	<0.01	5	1500	36	10	<20	127	0.03	<10	34	<10	5	91
20	E192490	1.5	1.27	20	320	<5	2.58	1	12	85	1217	4.36	<10	0.89	914	38	0.04	4	1460	34	<5	<20	195	0.05	<10	59	<10	5	94
21	E192491	1.5	1.20	15	245	<5	2.48	1	13	80	1206	4.15	<10	0.80	939	46	0.03	6	1380	32	5	<20	191	0.04	<10	49	<10	5	92
22	E192492	<0.2	1.14	40	275	5	0.69	<1	7	100	5	2.17	<10	0.59	566	2	0.11	7	970	28	<5	<20	95	0.16	<10	49	<10	3	45
23	E192493	2.3	1.34	25	140	<5	2.80	1	13	92	1909	3.74	<10	0.96	1106	46	0.01	5	1390	38	<5	<20	194	0.04	<10	41	<10	6	123
24	E192494	2.1	1.23	10	70	<5	3.07	1	22	105	1315	5.53	<10	0.76	1123	39	0.01	6	1490	40	<5	<20	192	0.05	<10	38	<10	4	83
25	E192495	1.4	1.29	30	135	<5	3.72	<1	11	73	1041	3.05	<10	0.87	1301	49	0.01	4	1530	30	5	<20	176	0.04	<10	28	<10	6	83

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	E192496	1.4	1.38	35	150	<5	3.48	1	11	84	970	3.13	<10	0.93	1259	40	<0.01	5	1560	34	10	<20	178	0.04	<10	31	<10	7	88
27	E192497	2.3	1.89	40	105	<5	2.15	<1	17	78	1435	4.67	<10	1.29	1224	49	<0.01	5	1710	44	5	<20	82	0.04	<10	37	<10	6	119
28	E192498	2.8	1.26	40	90	<5	2.75	<1	13	74	1931	3.46	<10	0.81	1082	46	<0.01	5	1480	40	<5	<20	91	0.03	<10	27	<10	5	84
29	E192499	1.7	0.90	40	70	<5	5.98	2	12	112	967	3.00	<10	0.59	1779	60	<0.01	6	1040	40	10	<20	203	0.04	<10	21	<10	6	61
30	E192500	1.5	1.13	45	80	<5	3.98	1	14	79	1066	3.76	<10	0.72	1321	41	0.02	4	1460	36	<5	<20	210	0.04	<10	35	<10	6	83
31	E192501	1.4	1.22	30	145	<5	2.57	<1	14	79	1028	4.01	<10	0.81	1155	35	0.03	5	1560	30	<5	<20	154	0.06	<10	48	<10	4	88
32	E192502	1.0	0.86	30	135	<5	7.84	<1	8	65	707	2.43	<10	0.57	1743	43	0.02	3	1140	22	10	<20	423	0.05	<10	35	<10	6	57
33	E192503	1.9	0.93	25	100	<5	4.36	1	14	83	1870	3.63	<10	0.63	1174	37	0.03	5	1120	134	<5	<20	249	0.06	<10	51	<10	6	75
34	E192504	1.4	1.14	25	215	<5	2.82	1	13	77	1386	4.09	<10	0.83	1059	33	0.04	6	1380	66	<5	<20	207	0.08	<10	63	<10	5	120
35	E192505	2.5	1.19	25	180	<5	1.84	1	14	93	2348	4.63	<10	0.87	834	23	0.03	5	1290	52	<5	<20	135	0.08	<10	75	<10	6	121
QC DATA:																													
Repeat:																													
1	E192471	2.4	1.45	30	140	<5	1.82	<1	13	73	1411	4.00	<10	1.06	776	40	0.02	5	1510	42	<5	<20	100	0.06	<10	52	<10	4	72
10	E192480	2.4	1.31	35	105	<5	2.79	<1	17	92	2075	3.67	<10	0.89	1024	51	<0.01	6	1310	36	<5	<20	137	0.03	<10	31	<10	5	63
19	E192489	2.2	1.42	35	145	<5	2.36	<1	14	94	1754	3.49	<10	1.00	953	35	0.01	6	1550	40	5	<20	137	0.04	<10	36	<10	7	94
Resplit:																													
1	E192471	2.4	1.43	30	135	<5	2.04	<1	14	92	1450	3.96	<10	1.00	865	47	0.02	6	1460	48	<5	<20	140	0.07	<10	53	<10	6	68
Standard:																													
Pb113		10.9	0.28	70	70	<5	1.84	44	3	6	2298	1.14	<10	0.15	1516	67	0.02	7	100	5518	20	<20	81	<0.01	<10	14	<10	<1	6979

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

JJ/jl
df/5566
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5563

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07084
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37411	0.50	0.015
2	G37412	0.71	0.021
3	G37413	0.93	0.027
4	G37414	0.84	0.024
5	G37415	0.83	0.024
6	G37416	0.66	0.019
7	G37417	0.74	0.022
8	G37418	0.87	0.025
9	G37419	0.66	0.019
10	G37420	0.49	0.014
11	G37421	0.88	0.026
12	G37422	0.49	0.014
13	G37423	0.54	0.016
14	G37424	0.70	0.020
15	G37425	0.81	0.024
16	G37426	0.73	0.021
17	G37427	1.57	0.046
18	G37428	0.54	0.016
19	G37429	1.21	0.035
20	G37430	0.83	0.024
21	G37431	0.66	0.019
22	G37432	<0.03	<0.001
23	G37433	0.55	0.016
24	G37434	0.55	0.016
25	G37435	0.56	0.016
26	G37436	0.67	0.020
27	G37437	0.55	0.016
28	G37438	0.47	0.014

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5563 17-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G37439	0.77	0.022
30	G37440	0.60	0.017
31	G37441	0.59	0.017
32	G37442	1.07	0.031
33	G37443	0.33	0.010
34	G37444	0.62	0.018
35	G37445	0.59	0.017
QC DATA:			
Repeat:			
1	G37411	0.50	0.015
3	G37413	0.92	0.027
10	G37420	0.50	0.015
19	G37429	1.17	0.034
32	G37442	1.01	0.029
Resplits:			
1	G37411	0.48	0.014
Standard:			
SI25		1.81	0.053

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

19-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5563

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07084
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37411	1.6	1.44	20	200	<5	2.07	<1	11	106	1437	4.54	<10	1.21	1047	31	0.04	5	1490	34	10	<20	194	0.03	<10	87	<10	3	70
2	G37412	3.2	1.24	20	75	<5	2.31	<1	12	143	2005	4.59	<10	0.86	1170	34	<0.01	5	1160	34	10	<20	168	0.03	<10	33	<10	2	90
3	G37413	3.6	0.94	25	45	<5	1.20	4	13	139	2989	4.12	<10	0.53	751	56	<0.01	5	1060	40	<5	<20	75	0.02	<10	19	<10	1	206
4	G37414	2.8	0.95	20	90	<5	1.73	3	14	150	2449	4.50	<10	0.56	1058	53	0.01	7	1020	32	10	<20	116	0.02	<10	30	<10	<1	213
5	G37415	3.2	0.99	25	95	<5	1.93	3	14	191	2575	4.59	<10	0.56	1149	83	0.01	7	970	36	<5	<20	138	0.03	<10	32	<10	1	218
6	G37416	2.0	0.53	45	40	<5	0.21	1	19	140	1382	5.92	<10	0.21	284	180	0.02	21	1010	40	<5	<20	16	0.02	<10	9	<10	<1	196
7	G37417	2.3	1.33	30	90	<5	3.58	1	10	133	1995	3.95	<10	0.94	1832	47	<0.01	5	1040	46	10	<20	185	0.03	<10	27	<10	2	175
8	G37418	2.8	0.47	300	70	<5	0.51	17	16	112	1369	>10	<10	0.04	89	109	0.03	17	2570	168	25	<20	25	0.04	<10	6	<10	<1	2081
9	G37419	1.7	1.00	20	160	<5	2.35	2	9	133	1548	3.93	<10	0.63	1249	51	0.01	5	1060	36	5	<20	170	0.03	<10	32	<10	3	228
10	G37420	1.6	1.04	20	190	<5	2.92	3	9	108	1347	3.96	<10	0.65	1445	34	0.01	6	1250	48	<5	<20	182	0.03	<10	36	<10	2	214
11	G37421	2.8	1.08	25	85	<5	1.72	2	12	124	2205	3.72	<10	0.77	1058	117	<0.01	6	1040	42	<5	<20	99	0.02	<10	30	<10	2	155
12	G37422	1.9	1.25	35	85	<5	1.56	2	12	129	1424	4.43	<10	0.79	1102	57	<0.01	6	1270	60	10	<20	82	0.03	<10	33	<10	2	210
13	G37423	1.7	1.40	30	90	<5	2.14	<1	12	117	1263	4.59	<10	0.89	1412	39	<0.01	6	1370	44	<5	<20	100	0.03	<10	32	<10	2	180
14	G37424	2.4	1.43	45	75	<5	2.33	<1	12	161	1729	5.43	<10	0.88	1253	42	<0.01	7	1170	50	<5	<20	104	0.04	<10	34	<10	2	97
15	G37425	4.7	1.39	35	55	<5	1.51	<1	10	146	2524	5.81	<10	0.85	1230	27	<0.01	7	1060	42	<5	<20	57	0.03	<10	30	<10	2	122
16	G37426	3.7	0.48	75	50	<5	0.22	<1	18	130	1587	6.28	<10	0.12	141	107	0.03	21	1090	40	<5	<20	22	0.02	<10	9	<10	<1	87
17	G37427	0.2	0.76	1940	85	20	0.88	12	30	24	54	4.77	10	1.99	672	5	0.17	114	1190	20	10	<20	70	0.11	<10	23	<10	8	57
18	G37428	1.6	1.23	25	335	<5	2.50	<1	12	112	1364	5.01	<10	0.79	1196	31	0.03	6	1410	40	<5	<20	185	0.06	<10	66	<10	4	169
19	G37420	3.7	1.21	30	65	<5	1.78	2	12	183	3024	4.41	<10	0.86	904	39	0.01	7	1010	40	5	<20	112	0.03	<10	35	<10	2	89
20	G37430	3.1	1.21	40	150	<5	1.06	<1	12	121	2685	4.55	<10	0.86	772	66	0.04	5	1010	40	<5	<20	94	0.05	<10	75	<10	2	158
21	G37431	2.3	1.07	25	125	<5	1.56	2	13	99	1691	4.47	<10	0.71	1006	56	0.02	6	1350	34	<5	<20	119	0.05	<10	51	<10	2	179
22	G37432	<0.2	1.07	35	285	25	0.59	<1	6	96	7	2.29	<10	0.60	558	2	0.11	7	920	20	5	<20	90	0.14	<10	48	<10	4	48
23	G37433	1.9	0.38	230	40	<5	0.23	3	18	125	1601	6.26	<10	0.06	89	223	0.03	11	1150	42	35	<20	26	0.02	<10	8	<10	<1	99
24	G37434	2.0	1.13	20	245	<5	2.15	1	13	136	1449	5.00	<10	0.78	1246	78	0.03	6	1300	42	<5	<20	185	0.06	<10	77	<10	3	190
25	G37435	2.0	1.07	30	185	<5	1.95	2	12	155	1617	4.46	<10	0.66	1117	50	0.02	8	1200	38	<5	<20	162	0.04	<10	47	<10	4	165

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37436	2.1	1.05	30	240	<5	1.92	1	11	104	1843	4.33	<10	0.73	1062	69	0.02	7	1120	38	15	<20	161	0.04	<10	61	<10	4	137
27	G37437	2.0	1.17	35	260	<5	1.81	<1	11	149	1539	4.28	<10	0.78	1135	62	0.01	7	1240	40	<5	<20	133	0.04	<10	40	<10	3	135
28	G37438	1.7	1.10	35	205	<5	1.90	<1	10	123	1263	3.82	<10	0.71	1150	34	<0.01	5	1270	32	<5	<20	146	0.04	<10	30	<10	3	122
29	G37439	2.7	1.08	35	70	<5	1.99	<1	12	126	1902	4.06	<10	0.68	1120	66	<0.01	7	1030	40	10	<20	109	0.03	<10	24	<10	3	98
30	G37440	2.3	1.26	40	90	<5	1.85	<1	10	149	1810	3.69	<10	0.76	1121	37	<0.01	7	1050	36	5	<20	89	0.02	<10	24	<10	4	105
31	G37441	2.5	0.92	40	95	<5	1.98	<1	9	127	1778	2.83	<10	0.51	949	37	<0.01	6	880	30	5	<20	91	0.02	<10	16	<10	5	73
32	G37442	5.3	1.39	35	65	<5	1.18	<1	12	146	3816	5.16	<10	0.75	922	39	<0.01	8	870	44	<5	<20	52	0.03	<10	28	<10	2	113
33	G37443	1.7	1.01	35	205	<5	2.30	<1	8	73	948	2.63	<10	0.53	1051	17	<0.01	4	1100	40	5	<20	134	0.04	<10	15	<10	5	69
34	G37444	2.8	0.53	45	55	<5	0.34	<1	21	114	1409	7.18	<10	0.07	75	246	0.04	6	1690	74	<5	<20	34	0.03	<10	12	<10	<1	44
35	G37445	3.2	1.34	40	125	<5	1.73	<1	10	95	2200	3.74	<10	0.72	870	129	<0.01	4	1010	40	10	<20	90	0.04	<10	22	<10	5	67
QC DATA:																													
Repeat:																													
1	G37411	1.6	1.56	15	220	<5	2.18	1	12	115	1539	4.81	<10	1.30	1108	32	0.05	6	1570	36	10	<20	202	0.03	<10	95	<10	3	74
6	G37416	<0.2	0.53	30	45	<5	0.20	1	19	138	1356	5.74	<10	0.21	279	163	0.02	21	980	36	<5	<20	23	0.02	<10	8	<10	<1	188
10	G37420	1.6	1.00	25	195	<5	2.95	3	9	112	1367	3.95	<10	0.64	1452	36	0.01	4	1270	48	<5	<20	184	0.03	<10	34	<10	2	219
19	G37420	3.5	1.22	50	85	<5	1.78	1	13	190	2972	4.42	<10	0.85	900	44	0.01	7	1040	46	<5	<20	120	0.04	<10	36	<10	4	91
Resplit:																													
1	G37411	1.8	1.52	15	175	<5	2.11	<1	12	91	1564	4.71	<10	1.29	1092	31	0.04	7	1610	44	15	<20	211	0.03	<10	93	<10	5	74
Standard:																													
Pb113		11.0	0.27	40	50	<5	1.72	42	3	6	2293	1.07	<10	0.12	1457	74	0.02	3	100	5510	20	<20	74	0.02	<10	8	10	<1	6998

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

JJ/jl
df/5560
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5564

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

18-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07085
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37446	0.37	0.011
2	G37447	0.47	0.014
3	G37448	3.30	0.096
4	G37449	0.90	0.026
5	G37450	0.24	0.007
6	G37451	0.38	0.011
7	G37452	0.53	0.015
8	G37453	0.30	0.009
9	G37454	1.30	0.038
10	G37455	0.34	0.010
11	G37456	0.40	0.012
12	G37457	0.87	0.025
13	G37458	1.09	0.032
14	G37459	<0.03	<0.001
15	G37460	0.35	0.010
16	G37461	0.33	0.010
17	G37462	0.38	0.011
18	G37463	0.32	0.009
19	G37464	0.36	0.010
20	G37465	0.93	0.027
21	G37466	0.81	0.024
22	G37467	0.95	0.028
23	G37468	0.35	0.010
24	G37469	0.34	0.010

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 5564 18-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
25	G37470	0.76	0.022
26	G37471	0.75	0.022
27	G37472	0.66	0.019
28	G37473	0.20	0.006
29	G37474	0.55	0.016
30	G37475	0.29	0.008
31	G37476	0.43	0.013
32	G37477	0.36	0.010
33	G37478	0.53	0.015
34	G37479	1.80	0.052
35	G37480	1.18	0.034
QC DATA:			
Repeat:			
1	G37446	0.40	0.012
3	G37448	3.18	0.093
9	G37454	1.29	0.038
10	G37455	0.38	0.011
13	G37458	1.06	0.031
19	G37464	0.34	0.010
34	G37479	1.79	0.052
35	G37480	1.13	0.033
Resplits:			
1	G37446	0.41	0.012
Standard:			
SI25		1.82	0.053
OXK48		3.53	0.103

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

19-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5564

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07085
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37446	2.2	0.77	35	165	<5	2.23	<1	7	119	1329	3.47	<10	0.40	803	23	0.01	5	960	32	<5	<20	133	0.04	<10	26	<10	3	43
2	G37447	2.3	0.83	30	95	<5	1.99	<1	10	90	1338	3.95	<10	0.51	660	22	0.02	5	1020	32	10	<20	138	0.05	<10	32	<10	3	48
3	G37448	9.8	0.28	35	45	<5	1.11	<1	11	196	8822	2.68	<10	0.06	279	23	<0.01	7	<10	40	<5	<20	65	0.01	<10	5	<10	1	12
4	G37449	3.5	0.69	35	75	<5	1.58	<1	7	163	2889	2.34	<10	0.37	513	27	<0.01	6	680	28	<5	<20	96	0.04	<10	18	<10	3	34
5	G37450	1.0	0.76	30	190	<5	3.09	<1	8	86	628	3.36	<10	0.51	829	21	0.03	4	960	30	5	<20	849	0.07	<10	32	<10	5	48
6	G37451	1.5	0.72	30	65	<5	2.75	<1	10	82	973	3.50	<10	0.49	660	22	0.03	3	960	32	<5	<20	953	0.08	<10	30	<10	5	43
7	G37452	2.6	0.69	40	110	<5	2.26	<1	8	138	1881	2.32	<10	0.36	599	32	<0.01	6	830	26	5	<20	135	0.05	<10	13	<10	5	31
8	G37453	1.4	0.85	30	150	<5	2.07	<1	9	80	996	3.22	<10	0.51	603	29	0.01	4	1020	28	<5	<20	123	0.06	<10	21	<10	4	45
9	G37454	4.9	0.88	45	70	<5	1.39	<1	11	140	3773	3.40	<10	0.53	572	92	<0.01	5	670	30	5	<20	56	0.04	<10	16	<10	2	46
10	G37455	2.0	0.84	30	140	<5	3.04	<1	8	104	1587	3.06	<10	0.50	809	12	0.02	4	1020	28	<5	<20	204	0.07	<10	22	<10	5	42
11	G37456	0.9	1.20	10	120	<5	1.74	<1	14	24	3971	3.56	<10	1.06	731	8	0.16	15	1310	38	5	<20	119	0.14	<10	173	<10	8	49
12	G37457	3.8	0.74	35	55	<5	1.54	<1	18	108	2905	4.18	<10	0.46	476	16	0.02	6	770	30	<5	<20	104	0.06	<10	20	<10	3	39
13	G37458	7.2	0.77	30	60	<5	1.62	<1	15	107	5570	4.99	<10	0.45	509	16	0.03	5	760	46	<5	<20	119	0.06	<10	29	<10	2	47
14	G37459	<0.2	1.06	45	270	25	0.62	<1	6	106	8	2.26	<10	0.58	546	2	0.11	7	940	32	5	<20	92	0.14	<10	47	<10	4	49
15	G37460	1.4	0.81	40	100	<5	2.10	<1	9	121	1100	3.34	<10	0.49	610	24	0.02	5	940	26	<5	<20	136	0.06	<10	24	<10	4	48
16	G37461	1.7	0.84	50	70	<5	2.13	<1	10	174	1237	3.48	<10	0.46	659	33	0.01	6	870	34	<5	<20	129	0.06	<10	22	<10	5	43
17	G37462	1.8	0.81	30	85	<5	2.34	<1	11	104	1236	4.04	<10	0.50	649	27	0.03	5	1060	36	<5	<20	158	0.07	<10	31	<10	5	42
18	G37463	1.3	0.87	40	90	<5	1.64	<1	10	126	1018	4.20	<10	0.55	542	23	0.03	5	990	32	<5	<20	125	0.07	<10	37	<10	5	47
19	G37464	1.5	0.90	45	100	<5	1.54	<1	9	104	1131	4.05	<10	0.59	518	24	0.03	5	980	32	<5	<20	112	0.06	<10	31	<10	3	48
20	G37465	3.3	0.83	35	60	<5	1.94	<1	13	128	3193	3.39	<10	0.54	530	79	0.02	7	750	28	5	<20	138	0.05	<10	26	<10	4	42
21	G37466	3.4	0.76	40	60	<5	1.13	<1	11	158	2488	3.45	<10	0.46	377	80	0.02	6	720	30	5	<20	67	0.05	<10	26	<10	4	38
22	G37467	4.2	0.66	45	60	<5	1.58	1	10	165	3309	3.23	<10	0.35	397	37	0.01	9	670	30	15	<20	80	0.03	<10	21	<10	5	30
23	G37468	1.6	1.00	35	95	<5	2.63	<1	10	126	1094	3.37	<10	0.62	771	41	<0.01	5	1010	34	10	<20	149	0.04	<10	21	<10	6	49
24	G37469	1.9	1.09	50	110	<5	2.42	<1	9	127	1230	3.36	<10	0.66	800	42	0.01	7	1020	34	10	<20	121	0.04	<10	24	<10	4	53
25	G37470	3.8	0.91	85	50	<5	2.17	<1	14	141	1539	4.71	<10	0.57	845	60	<0.01	5	980	50	<5	<20	68	0.06	<10	16	<10	1	78

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37471	5.1	0.94	40	60	<5	1.66	<1	10	129	2300	3.45	<10	0.69	674	13	<0.01	5	960	54	10	<20	50	0.04	<10	15	<10	3	67
27	G37472	5.1	1.12	40	65	<5	1.51	<1	9	128	2207	3.21	<10	0.86	704	17	<0.01	3	990	54	10	<20	47	0.04	<10	17	<10	3	79
28	G37473	1.3	0.88	40	160	<5	2.75	<1	6	82	538	2.46	<10	0.49	842	14	<0.01	3	1110	28	5	<20	129	0.04	<10	16	<10	4	57
29	G37474	2.5	0.71	35	95	<5	2.16	<1	10	109	1745	3.02	<10	0.41	664	21	<0.01	5	890	30	<5	<20	104	0.05	<10	19	<10	3	55
30	G37475	1.5	0.92	30	135	<5	2.01	<1	9	78	988	3.42	<10	0.64	698	21	0.03	4	1070	36	<5	<20	150	0.06	<10	35	<10	4	71
31	G37476	1.7	0.73	30	65	<5	2.47	<1	9	88	1251	3.06	<10	0.45	744	32	0.02	4	980	28	10	<20	155	0.06	<10	25	<10	4	57
32	G37477	1.3	0.78	30	135	<5	2.46	<1	8	74	954	2.90	<10	0.43	765	18	0.02	4	1220	28	<5	<20	136	0.06	<10	23	<10	5	51
33	G37478	1.7	0.80	30	205	<5	2.76	<1	7	74	1698	3.12	<10	0.47	791	18	0.01	4	1040	24	10	<20	168	0.06	<10	23	<10	5	52
34	G37479	6.2	0.26	35	60	<5	1.49	<1	7	113	6096	1.98	<10	0.05	339	12	<0.01	6	340	38	<5	<20	63	0.03	<10	4	<10	4	14
35	G37480	4.3	0.29	40	30	<5	1.18	<1	7	146	3927	2.21	<10	0.02	258	18	<0.01	5	670	20	<5	<20	37	0.03	<10	5	<10	2	5
QC DATA:																													
Repeat:																													
1	G37446	2.2	0.79	30	175	<5	2.23	<1	7	122	1344	3.45	<10	0.40	802	23	0.02	4	940	30	<5	<20	140	0.05	<10	26	<10	4	43
10	G37455	2.1	0.86	30	145	<5	3.06	<1	8	106	1607	3.08	<10	0.51	814	12	0.02	4	1030	28	<5	<20	213	0.07	<10	23	<10	6	43
19	G37464	1.5	0.91	35	110	<5	1.57	<1	9	108	1134	4.12	<10	0.59	527	24	0.03	6	1010	34	5	<20	110	0.06	<10	32	<10	4	47
Resplit:																													
1	G37446	2.4	0.87	35	170	<5	2.21	<1	9	121	1401	3.73	<10	0.45	821	23	0.01	6	1020	34	5	<20	141	0.05	<10	29	<10	5	48
Standard:																													
Pb113		10.5	0.27	40	65	<5	1.78	39	1	6	2234	1.10	<10	0.10	1492	71	0.02	2	80	5516	25	<20	83	0.02	<10	8	<10	<1	7052

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

JJ/jl/sa
df/5560
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5565

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

18-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07087
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	E192541	0.44	0.013
2	E192542	0.26	0.008
3	E192543	0.22	0.006
4	E192544	0.16	0.005
5	E192545	0.16	0.005
6	E192546	0.23	0.007
7	E192547	0.27	0.008
8	E192548	0.46	0.013
9	E192549	0.45	0.013
10	E192550	0.30	0.009
11	E192551	0.22	0.006
12	E192552	0.27	0.008
13	E192553	<0.03	<0.001
14	E192554	0.36	0.010
15	E192555	0.50	0.015
16	E192556	0.21	0.006
17	E192557	0.19	0.006
18	E192558	0.22	0.006
19	E192559	0.16	0.005
20	E192560	0.20	0.006
21	E192561	0.33	0.010
22	E192562	0.74	0.022
23	E192563	0.48	0.014
24	E192564	<0.03	<0.001
25	E192565	0.53	0.015
26	E192566	0.27	0.008
27	E192567	0.23	0.007

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 5565 18-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	E192568	0.26	0.008
29	E192569	1.88	0.055
30	E192570	0.45	0.013
31	E192571	0.57	0.017
32	E192572	0.16	0.005
33	E192573	0.33	0.010
34	E192574	0.18	0.005
35	E192575	0.38	0.011
QC DATA:			
Repeat:			
1	E192541	0.46	0.013
10	E192550	0.35	0.010
19	E192559	0.15	0.004
Resplits:			
1	E192541	0.42	0.012
Standard:			
SI25		1.80	0.052

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

20-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5565

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07087
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	E192541	1.4	0.77	10	60	<5	3.23	1	10	67	1702	1.98	<10	0.49	494	292	0.03	2	800	28	<5	<20	240	0.07	<10	30	<10	7	47
2	E192542	10.4	0.62	<5	45	<5	2.23	6	11	78	1951	4.83	<10	0.27	722	79	0.01	6	800	140	5	<20	37	0.04	<10	17	<10	4	133
3	E192543	1.5	1.08	<5	125	<5	2.93	2	9	86	999	2.46	<10	0.65	952	37	0.01	3	920	38	5	<20	99	0.07	<10	23	<10	6	70
4	E192544	1.6	0.87	<5	115	<5	2.79	8	9	73	733	2.55	<10	0.49	799	77	0.02	5	940	82	10	<20	49	0.06	<10	23	<10	6	348
5	E192545	0.7	0.84	<5	175	<5	3.23	2	10	75	767	2.60	<10	0.48	712	35	0.03	4	1000	26	5	<20	149	0.07	<10	35	<10	6	63
6	E192546	0.7	0.98	<5	145	<5	3.18	2	9	76	793	2.28	<10	0.56	810	30	0.02	5	1010	28	15	<20	128	0.06	<10	24	<10	7	63
7	E192547	0.9	0.68	<5	80	<5	4.57	2	7	80	1157	1.56	<10	0.37	745	31	0.02	3	750	34	<5	<20	181	0.06	<10	16	<10	6	60
8	E192548	1.2	0.90	<5	100	<5	4.02	2	9	58	1454	1.93	<10	0.46	778	38	0.02	3	870	28	10	<20	133	0.05	<10	18	<10	5	50
9	E192549	1.6	0.73	5	130	<5	3.71	2	8	131	2094	1.89	<10	0.40	776	51	0.01	3	600	30	<5	<20	85	0.06	<10	14	<10	4	46
10	E192550	0.9	0.82	<5	155	<5	3.63	2	8	80	1041	2.17	<10	0.40	833	29	0.01	4	860	24	10	<20	121	0.06	<10	20	<10	5	55
11	E192551	0.7	0.84	<5	165	<5	3.94	1	8	69	873	2.05	<10	0.42	849	45	0.02	3	910	22	<5	<20	156	0.07	<10	21	<10	6	59
12	E192552	0.9	0.97	<5	200	<5	2.90	2	9	85	1052	2.54	<10	0.57	813	193	0.03	4	890	34	10	<20	110	0.08	<10	30	<10	5	95
13	E192553	<0.2	1.03	<5	250	40	0.63	<1	8	111	7	2.19	<10	0.55	539	3	0.12	5	780	28	<5	<20	98	0.12	<10	45	<10	5	42
14	E192554	0.8	1.08	5	355	<5	1.98	2	9	72	806	2.67	<10	0.74	659	184	0.04	5	920	30	10	<20	155	0.08	<10	44	<10	5	84
15	E192555	1.4	1.02	<5	160	<5	2.62	3	11	69	1407	2.79	<10	0.69	844	65	0.03	4	910	36	5	<20	90	0.08	<10	37	<10	4	104
16	E192556	1.1	0.95	<5	305	<5	2.32	1	9	64	1049	2.69	<10	0.60	625	66	0.04	3	970	26	<5	<20	128	0.08	<10	44	<10	5	63
17	E192557	0.9	1.34	<5	135	<5	1.57	2	14	67	715	3.60	<10	1.00	547	38	0.04	6	1350	28	5	<20	117	0.03	<10	64	<10	7	53
18	E192558	1.0	1.41	<5	125	<5	2.41	2	14	42	831	3.50	<10	1.07	740	30	0.03	6	1340	32	15	<20	172	0.04	<10	55	<10	8	58
19	E192559	0.7	1.26	<5	150	<5	1.95	1	13	38	565	3.53	<10	0.93	667	20	0.04	5	1430	28	<5	<20	151	0.04	<10	58	<10	6	60
20	E192560	0.9	1.48	5	150	<5	1.78	2	12	63	620	3.28	<10	1.09	796	23	0.02	7	1400	36	15	<20	107	0.03	<10	54	<10	6	81
21	E192561	1.2	1.42	<5	105	<5	1.67	2	13	65	782	3.61	<10	1.13	803	29	0.04	5	1320	32	10	<20	186	0.03	<10	62	<10	5	79
22	E192562	1.0	1.52	<5	160	<5	2.08	2	11	55	743	3.27	<10	1.18	836	36	0.02	6	1360	30	5	<20	108	0.03	<10	53	<10	6	70
23	E192563	1.8	1.41	<5	160	<5	2.38	2	12	95	1712	3.33	<10	1.00	714	88	0.02	5	1240	32	15	<20	156	0.03	<10	48	<10	7	62
24	E192564	<0.2	1.12	<5	245	20	0.70	<1	7	136	8	2.30	<10	0.56	557	3	0.13	6	790	24	<5	<20	102	0.12	<10	47	<10	3	43
25	E192565	1.3	1.27	<5	110	<5	1.72	2	14	71	1002	3.93	<10	0.91	599	34	0.04	6	1310	30	10	<20	145	0.03	<10	59	<10	5	54

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	E192566	1.1	1.44	<5	140	<5	2.31	<1	14	56	801	3.12	<10	1.06	748	45	0.03	6	1420	30	5	<20	175	0.02	<10	49	<10	6	58
27	E192567	1.2	1.53	<5	115	<5	2.76	2	16	59	824	3.90	<10	1.10	927	41	0.02	5	1380	36	10	<20	174	0.03	<10	51	<10	6	70
28	E192568	1.3	1.56	<5	95	<5	2.41	2	15	59	869	3.72	<10	1.18	851	125	0.03	5	1330	68	10	<20	181	0.04	<10	56	<10	7	105
29	E192569	3.9	1.17	35	60	<5	1.03	2	22	61	8544	4.21	10	0.58	202	597	0.04	63	120	72	30	<20	53	0.01	<10	44	<10	5	70
30	E192570	13.9	1.18	10	50	<5	3.87	2	14	61	936	3.88	<10	0.85	1294	54	0.02	6	1190	104	15	<20	188	0.03	<10	41	<10	8	81
31	E192571	1.6	1.38	<5	105	<5	2.22	2	15	53	806	3.37	<10	0.97	732	47	0.02	5	1420	36	5	<20	146	0.02	<10	46	<10	6	86
32	E192572	1.9	1.50	10	95	<5	2.41	2	15	49	551	3.66	<10	1.12	835	36	0.03	6	1450	40	15	<20	182	0.03	<10	54	<10	9	66
33	E192573	6.1	1.09	10	50	<5	3.12	3	14	68	1070	3.14	<10	0.69	1020	46	0.01	3	1240	162	<5	<20	146	0.02	<10	34	<10	8	149
34	E192574	1.6	1.37	<5	135	<5	2.04	2	13	65	697	3.65	<10	0.95	740	44	0.04	5	1360	74	5	<20	130	0.03	<10	61	<10	5	111
35	E192575	1.4	1.52	<5	110	<5	2.18	8	14	37	672	3.68	<10	1.10	768	39	0.03	6	1320	132	10	<20	147	0.04	<10	62	<10	6	335
QC DATA:																													
Repeat:																													
1	E192541	1.4	0.77	<5	60	<5	3.15	2	10	67	1684	1.94	<10	0.48	484	281	0.03	2	780	26	<5	<20	239	0.07	<10	29	<10	6	45
10	E192550	0.9	0.86	<5	165	<5	3.73	2	8	84	1064	2.23	<10	0.42	856	35	0.01	5	900	26	15	<20	127	0.05	<10	22	<10	6	57
19	E192559	0.8	1.28	<5	145	<5	1.95	2	14	38	564	3.54	<10	0.93	666	18	0.04	6	1430	28	10	<20	154	0.04	<10	59	<10	6	62
Resplit:																													
1	E192541	1.4	0.79	5	65	<5	3.05	2	10	62	1733	1.97	<10	0.49	476	283	0.02	4	850	28	5	<20	239	0.07	<10	30	<10	5	49
Standard:																													
Pb113		11.6	0.28	45	75	<5	1.68	42	2	6	2217	1.05	<10	0.09	1422	60	0.02	2	80	5036	25	<20	84	0.01	<10	7	<10	<1	6910

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5539S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5566

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

17-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07088
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37481	0.59	0.017
2	G37482	0.44	0.013
3	G37483	0.30	0.009
4	G37484	0.44	0.013
5	G37485	0.27	0.008
6	G37486	0.25	0.007
7	G37487	1.81	0.053
8	G37488	0.20	0.006
9	G37489	0.55	0.016
10	G37490	0.30	0.009
11	G37491	0.99	0.029
12	G37492	0.42	0.012
13	G37493	0.21	0.006
14	G37494	0.32	0.009
15	G37495	0.49	0.014
16	G37496	0.16	0.005
17	G37497	0.54	0.016
18	G37498	0.31	0.009
19	G37499	<0.03	<0.001
20	G37500	0.23	0.007
21	G37501	0.29	0.008
22	G37502	0.28	0.008
23	G37503	0.31	0.009
24	G37504	0.48	0.014
25	G37505	0.41	0.012
26	G37506	0.22	0.006
27	G37507	0.16	0.005

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5566 17-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G37508	0.14	0.004
29	G37509	0.23	0.007
30	G37510	0.31	0.009
31	G37511	0.32	0.009
32	G37512	0.64	0.019
33	G37513	0.35	0.010
34	G37514	0.14	0.004
35	G37515	0.16	0.005
QC DATA:			
Repeat:			
1	G37481	0.56	0.016
10	G37490	0.28	0.008
11	G37491	1.04	0.030
32	G37512	0.60	0.017
Resplits:			
1	G37481	0.61	0.018
Standard:			
SI25		1.79	0.052

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO-TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

19-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5566

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07088
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37481	2.6	0.52	<5	55	<5	1.42	<1	10	97	2568	2.40	<10	0.23	409	34	0.01	4	760	18	<5	<20	54	0.04	<10	11	<10	3	21
2	G37482	1.5	0.71	<5	85	<5	1.97	<1	10	104	1233	2.88	<10	0.39	585	33	0.02	4	800	20	<5	<20	96	0.05	<10	19	<10	5	35
3	G37483	1.0	0.61	<5	145	<5	2.18	<1	7	77	901	2.50	<10	0.28	555	18	0.02	3	930	18	<5	<20	91	0.05	<10	13	<10	5	29
4	G37484	1.8	0.58	<5	100	<5	2.46	1	8	81	1515	2.47	<10	0.27	574	117	0.01	3	820	22	<5	<20	100	0.05	<10	13	<10	5	27
5	G37485	0.8	0.70	10	170	<5	2.76	<1	9	74	707	2.80	<10	0.38	697	28	0.02	4	1010	18	<5	<20	271	0.05	<10	19	<10	6	38
6	G37486	1.1	0.71	10	125	<5	2.44	<1	8	108	914	2.20	<10	0.40	657	52	0.02	3	900	20	<5	<20	181	0.05	<10	16	<10	5	35
7	G37487	4.0	1.08	35	70	<5	1.07	2	23	57	8599	4.38	10	0.60	211	566	0.04	60	120	66	15	<20	57	0.04	<10	43	<10	6	74
8	G37488	1.0	0.79	10	120	<5	2.94	<1	9	81	796	2.77	<10	0.47	785	20	0.01	3	1000	26	<5	<20	125	0.06	<10	16	<10	9	40
9	G37489	2.0	0.67	<5	125	<5	2.79	<1	8	107	1714	2.43	<10	0.36	623	34	0.01	5	790	22	<5	<20	112	0.05	<10	13	<10	6	26
10	G37490	1.2	0.71	10	195	<5	2.79	<1	7	88	985	2.56	<10	0.34	633	22	0.02	4	950	18	<5	<20	129	0.06	<10	17	<10	6	33
11	G37491	4.1	0.52	10	75	<5	1.89	<1	11	130	3718	2.23	<10	0.19	463	16	<0.01	6	560	18	5	<20	79	0.03	<10	8	<10	6	19
12	G37492	1.6	0.75	5	205	<5	2.97	<1	10	91	1284	2.71	<10	0.40	703	29	0.02	3	900	24	<5	<20	160	0.07	<10	20	<10	7	40
13	G37493	0.8	0.83	5	240	<5	2.57	<1	8	73	774	2.75	<10	0.47	701	32	0.02	5	960	22	5	<20	189	0.06	<10	20	<10	6	47
14	G37494	1.5	0.94	5	180	<5	1.60	<1	9	86	1368	2.79	<10	0.58	533	26	0.02	4	950	22	<5	<20	112	0.06	<10	22	<10	6	50
15	G37495	1.9	0.93	5	120	<5	1.20	<1	12	111	1770	2.67	<10	0.57	481	24	0.01	4	940	38	<5	<20	111	0.06	<10	17	<10	10	51
16	G37496	0.6	0.66	10	325	<5	2.10	<1	8	79	570	2.68	<10	0.30	624	21	0.03	4	1100	28	<5	<20	165	0.07	<10	24	<10	6	37
17	G37497	2.4	0.87	10	85	<5	1.25	<1	11	82	2380	3.02	<10	0.54	511	27	0.03	3	840	42	<5	<20	104	0.07	<10	22	<10	7	60
18	G37498	1.0	0.94	10	115	<5	0.84	<1	10	93	956	2.99	<10	0.61	457	32	0.03	5	960	28	<5	<20	64	0.06	<10	25	<10	4	57
19	G37499	<0.2	1.12	10	275	25	0.65	<1	7	90	6	2.30	<10	0.59	561	4	0.12	8	910	24	<5	<20	94	0.14	<10	48	<10	3	43
20	G37500	1.0	0.87	15	270	<5	1.12	<1	8	77	732	2.85	<10	0.47	484	47	0.03	5	1140	28	5	<20	99	0.06	<10	23	<10	5	45
21	G37501	1.5	0.82	5	120	<5	0.80	<1	10	143	1477	2.66	<10	0.44	395	75	0.03	5	830	28	<5	<20	55	0.06	<10	19	<10	5	42
22	G37502	1.1	0.89	10	140	<5	0.74	<1	10	84	963	3.02	<10	0.51	409	46	0.03	4	1060	28	<5	<20	51	0.06	<10	26	<10	4	47
23	G37503	1.2	0.80	5	210	<5	1.26	<1	9	86	1305	3.11	<10	0.44	470	41	0.03	4	1000	24	<5	<20	111	0.06	<10	27	<10	5	43
24	G37504	1.8	0.88	10	170	<5	1.41	<1	10	74	1807	3.23	<10	0.57	545	199	0.03	3	980	26	<5	<20	101	0.06	<10	30	<10	6	46
25	G37505	2.0	0.89	10	140	<5	2.28	1	11	91	1895	3.13	<10	0.58	716	265	0.03	4	960	32	<5	<20	204	0.07	<10	29	<10	8	46

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37506	0.9	0.78	10	135	<5	1.46	<1	10	71	689	3.15	<10	0.41	551	89	0.03	2	1110	28	<5	<20	106	0.06	<10	25	<10	5	45
27	G37507	0.6	0.67	<5	290	<5	2.06	<1	8	67	482	3.05	<10	0.35	662	42	0.03	3	1060	24	<5	<20	147	0.07	<10	33	<10	5	44
28	G37508	0.4	0.71	10	435	<5	2.69	<1	8	78	449	2.95	<10	0.37	759	36	0.04	3	1040	26	<5	<20	242	0.08	<10	37	<10	7	41
29	G37509	0.8	0.74	10	220	<5	1.90	<1	8	89	866	2.57	<10	0.44	598	28	0.03	4	960	26	<5	<20	143	0.07	<10	29	<10	6	36
30	G37510	1.2	0.95	10	280	<5	1.47	<1	8	82	1057	2.81	<10	0.57	580	27	0.03	3	1040	24	<5	<20	144	0.07	<10	29	<10	6	44
31	G37511	1.3	0.91	10	165	<5	1.14	<1	8	79	1248	2.94	<10	0.56	514	29	0.02	4	1060	28	<5	<20	68	0.07	<10	30	<10	6	46
32	G37512	2.8	1.01	10	125	<5	1.36	<1	9	144	3267	2.66	<10	0.61	502	44	0.04	5	760	54	<5	<20	78	0.07	<10	31	<10	6	55
33	G37513	1.6	0.80	10	155	<5	1.92	1	10	92	1280	2.64	<10	0.48	571	46	0.02	5	1070	54	5	<20	114	0.06	<10	27	<10	8	51
34	G37514	0.6	0.84	15	130	<5	1.51	<1	11	83	442	2.65	<10	0.48	581	66	0.02	4	1090	36	5	<20	80	0.06	<10	20	<10	5	46
35	G37515	0.6	0.83	15	205	<5	1.53	<1	10	61	562	2.77	<10	0.50	576	45	0.02	4	1150	26	<5	<20	98	0.06	<10	25	<10	5	43
QC DATA:																													
Repeat:																													
1	G37481	2.8	0.49	<5	60	<5	1.37	<1	10	93	2507	2.33	<10	0.22	398	33	0.01	4	740	20	<5	<20	62	0.04	<10	11	<10	5	20
10	G37490	1.4	0.71	<5	175	<5	2.83	<1	7	86	1002	2.59	<10	0.34	642	21	0.02	3	980	18	<5	<20	130	0.06	<10	16	<10	6	33
Resplit:																													
1	G37481	2.9	0.51	<5	55	<5	1.26	<1	10	112	2530	2.49	<10	0.20	361	40	0.01	4	750	20	<5	<20	47	0.04	<10	11	<10	3	20
Standard:																													
Pb113		10.9	0.26	60	65	<5	1.78	38	2	5	2294	1.11	<10	0.10	1485	80	0.02	2	90.5410	15	<20	89	0.02	<10	8	<10	<1	6972	

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

JJ/jl
df/5566
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5567

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

18-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07090
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	E192576	0.25	0.007
2	E192577	0.27	0.008
3	E192578	0.28	0.008
4	E192579	0.20	0.006
5	E192580	0.35	0.010
6	E192581	0.23	0.007
7	E192582	0.25	0.007
8	E192583	0.29	0.008
9	E192584	0.29	0.008
10	E192585	0.21	0.006
11	E192586	0.30	0.009
12	E192587	0.13	0.004
13	E192588	0.13	0.004
14	E192589	0.13	0.004
15	E192590	0.67	0.020
16	E192591	0.27	0.008
17	E192592	0.83	0.024
18	E192593	0.34	0.010
19	E192594	0.27	0.008
20	E192595	0.20	0.006
21	E192596	<0.03	<0.001
22	E192597	0.36	0.010
23	E192598	0.47	0.014
24	E192599	0.49	0.014
25	E192600	0.25	0.007
26	E192601	0.29	0.008
27	E192602	0.60	0.017

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc.AS7-5567 18-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	E192603	0.45	0.013
29	E192604	0.33	0.010
30	E192605	0.27	0.008
31	E192606	0.35	0.010
32	E192607	0.33	0.010
33	E192608	0.29	0.008
34	E192609	0.28	0.008
35	E192610	0.28	0.008
QC DATA:			
Repeat:			
1	E192576	0.24	0.007
10	E192585	0.19	0.006
19	E192594	0.27	0.008
Resplits:			
1	E192576	0.19	0.006
Standard:			
SI25		1.80	0.052

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

19-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5567

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07090
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	E192576	0.9	1.32	15	135	<5	3.51	3	13	42	708	3.86	<10	1.04	840	22	0.04	2	1450	404	5	<20	243	0.03	<10	65	<10	6	175
2	E192577	1.0	1.49	15	105	<5	1.50	<1	13	70	875	3.86	<10	1.29	545	128	0.04	5	1450	68	5	<20	138	0.03	<10	79	<10	7	88
3	E192578	0.9	1.18	10	75	<5	1.18	<1	13	75	932	3.38	<10	0.95	420	88	0.03	5	1340	30	5	<20	90	0.02	<10	54	<10	5	56
4	E192579	0.6	1.30	10	195	<5	1.47	<1	16	63	678	4.19	<10	0.99	517	67	0.05	4	1540	30	<5	<20	128	0.03	<10	80	<10	5	60
5	E192580	4.3	1.21	15	100	<5	1.82	<1	14	97	1310	3.81	<10	0.93	660	39	0.02	6	1240	36	5	<20	138	0.02	<10	48	<10	5	58
6	E192581	0.8	1.45	20	80	<5	2.63	<1	15	73	693	4.01	<10	1.14	914	53	0.04	5	1410	32	5	<20	260	0.03	<10	62	<10	4	70
7	E192582	1.0	1.46	10	110	<5	1.26	<1	13	84	816	3.38	<10	1.19	558	83	0.04	6	1540	36	5	<20	112	0.03	<10	60	<10	6	73
8	E192583	3.2	1.17	30	50	<5	1.03	3	22	57	2580	3.67	20	0.61	200	203	0.03	10	470	68	15	<20	62	0.04	<10	47	<10	7	278
9	E192584	1.2	1.38	20	105	<5	1.13	<1	11	98	1059	3.27	<10	1.24	479	151	0.05	4	1420	36	10	<20	100	0.03	<10	67	<10	6	53
10	E192585	1.0	1.30	15	70	<5	1.87	<1	17	73	779	3.55	<10	1.07	706	63	0.01	6	1650	30	5	<20	86	0.04	<10	44	<10	5	48
11	E192586	1.1	1.32	10	95	<5	3.37	<1	15	78	890	3.01	<10	1.11	1016	62	<0.01	5	1440	28	10	<20	144	0.04	<10	34	<10	7	46
12	E192587	0.8	1.26	15	105	<5	1.86	<1	15	80	498	2.90	<10	1.15	751	27	<0.01	5	1360	30	10	<20	80	0.04	<10	32	<10	5	50
13	E192588	0.6	2.90	30	170	<5	3.95	<1	28	127	456	4.67	<10	3.25	1011	35	0.02	51	930	52	15	<20	228	0.15	<10	86	<10	6	50
14	E192589	1.2	2.96	30	145	<5	4.13	<1	30	141	500	4.91	<10	3.28	1045	25	0.02	49	1050	56	15	<20	232	0.15	<10	101	<10	6	62
15	E192590	3.8	1.30	15	95	<5	2.59	<1	19	96	2221	4.04	<10	0.91	812	93	0.01	5	1210	32	<5	<20	135	0.06	<10	40	<10	6	66
16	E192591	4.8	0.99	20	75	<5	2.74	5	13	87	917	3.19	<10	0.63	861	56	0.02	5	1450	198	<5	<20	156	0.05	<10	35	<10	6	335
17	E192592	3.8	0.92	20	80	<5	2.75	1	14	87	3745	2.72	<10	0.64	588	297	0.02	5	1000	36	5	<20	142	0.03	<10	35	<10	7	37
18	E192593	1.4	1.02	20	75	<5	3.62	<1	13	106	1277	2.43	<10	0.73	781	148	<0.01	5	1380	24	<5	<20	155	0.03	<10	29	<10	6	31
19	E192594	1.7	1.14	15	75	<5	3.88	<1	17	73	778	3.21	<10	0.77	1001	44	<0.01	5	1510	38	10	<20	169	0.04	<10	33	<10	7	62
20	E192595	1.1	1.34	20	135	<5	3.77	<1	13	66	853	3.78	<10	0.96	981	77	0.03	6	1480	32	<5	<20	263	0.05	<10	48	<10	6	64
21	E192596	<0.2	1.08	25	280	35	0.61	<1	7	89	4	2.17	<10	0.60	567	3	0.10	6	970	24	10	<20	88	0.14	<10	49	<10	3	45
22	E192597	1.6	1.25	20	80	<5	3.80	<1	18	74	1108	3.83	<10	0.88	1085	60	0.01	5	1500	34	<5	<20	199	0.04	<10	38	<10	6	53
23	E192598	2.5	1.37	15	160	<5	2.64	<1	14	60	1293	3.64	<10	1.01	802	60	0.04	4	1520	40	<5	<20	211	0.05	<10	50	<10	6	66
24	E192599	1.8	0.97	30	65	<5	3.00	<1	14	71	1187	3.07	<10	0.61	752	58	0.01	4	1400	34	<5	<20	145	0.03	<10	26	<10	6	47
25	E192600	1.2	1.42	15	115	<5	2.49	<1	16	62	891	3.57	<10	1.10	702	48	0.03	5	1540	30	5	<20	207	0.06	<10	53	<10	7	63

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	E192601	1.4	1.42	20	75	<5	2.28	<1	19	80	930	3.94	<10	1.11	766	64	0.03	4	1420	62	<5	<20	171	0.04	<10	53	<10	6	91
27	E192602	7.6	1.15	15	100	<5	4.47	3	12	65	1620	3.46	<10	0.80	1306	60	0.01	3	1090	116	<5	<20	288	0.03	<10	41	<10	5	175
28	E192603	2.8	1.22	15	100	<5	2.36	1	13	76	1375	3.98	<10	0.90	767	81	0.02	6	1340	44	5	<20	172	0.03	<10	51	<10	5	73
29	E192604	1.3	1.25	15	195	<5	2.72	1	14	66	823	3.78	<10	0.90	723	60	0.04	5	1540	30	15	<20	225	0.06	<10	58	<10	6	51
30	E192605	1.0	1.34	20	95	<5	1.76	<1	16	109	868	3.77	<10	0.91	593	74	0.04	6	1490	38	<5	<20	150	0.04	<10	54	<10	7	45
31	E192606	1.1	1.32	15	110	<5	1.77	<1	14	78	1048	3.61	<10	0.96	612	86	0.03	4	1540	32	<5	<20	142	0.04	<10	52	<10	6	48
32	E192607	1.2	1.35	25	100	<5	1.96	<1	16	67	1203	3.82	<10	0.99	638	74	0.03	4	1560	46	<5	<20	165	0.04	<10	49	<10	6	59
33	E192608	1.1	1.25	20	115	<5	2.31	<1	15	69	1020	3.37	<10	0.89	642	57	0.03	5	1510	30	5	<20	172	0.04	<10	48	<10	6	55
34	E192609	1.1	1.29	35	95	<5	2.68	1	14	72	799	3.61	<10	0.91	744	81	0.03	4	1490	48	<5	<20	193	0.06	<10	57	<10	7	56
35	E192610	1.7	1.34	20	75	<5	2.31	<1	17	94	1150	3.69	<10	0.97	813	90	0.02	5	1490	50	<5	<20	162	0.03	<10	47	<10	8	66
QC DATA:																													
Repeat:																													
1	E192576	0.8	1.35	10	135	<5	3.52	3	13	45	712	3.85	<10	1.06	841	24	0.04	4	1460	408	10	<20	253	0.03	<10	67	<10	7	175
10	E192585	0.9	1.35	25	70	<5	1.89	<1	17	76	784	3.58	<10	1.09	711	64	0.02	6	1680	30	5	<20	86	0.05	<10	46	<10	6	48
19	E192594	1.6	1.14	25	95	<5	3.80	<1	17	74	749	3.14	<10	0.75	975	42	<0.01	4	1480	40	5	<20	175	0.05	<10	32	<10	8	60
Resplit:																													
1	E192576	1.0	1.42	15	140	<5	3.73	2	13	51	840	4.01	<10	1.09	909	31	0.04	5	1500	430	5	<20	259	0.03	<10	69	<10	6	156
Standard:																													
Pb113		11.0	0.28	40	50	<5	1.85	42	3	6	2251	1.16	<10	0.10	1535	72	0.02	1	90	5584	15	<20	87	0.02	<10	9	<10	<1	6971

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

JJ/jl
df/5566
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5568

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

18-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07091
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	E192611	0.35	0.010
2	E192612	0.23	0.007
3	E192613	0.35	0.010
4	E192614	0.33	0.010
5	E192615	0.19	0.006
6	E192616	0.27	0.008
7	E192617	0.24	0.007
8	E192618	<0.03	<0.001
9	E192619	0.21	0.006
10	E192620	0.22	0.006
11	E192621	0.21	0.006
12	E192622	0.18	0.005
13	E192623	0.12	0.003
14	E192624	0.13	0.004
15	E192625	0.13	0.004
16	E192626	0.12	0.003
17	E192627	0.23	0.007
18	E192628	0.31	0.009
19	E192629	0.31	0.009
20	E192630	0.28	0.008
21	E192631	0.21	0.006
22	E192632	0.12	0.003
23	E192633	0.17	0.005
24	E192634	0.26	0.008
25	E192635	0.31	0.009
26	E192636	0.30	0.009
27	E192637	0.35	0.010

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 18-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	E192638	0.32	0.009
29	E192639	0.27	0.008
30	E192640	0.19	0.006
31	E192641	0.35	0.010
32	E192642	0.38	0.011
33	E192643	0.22	0.006
34	E192644	0.18	0.005
35	E192645	0.35	0.010

QC DATA:

Repeat:

1	E192611	0.36	0.010
10	E192620	0.23	0.007
19	E192629	0.30	0.009

Resplits:

1	E192611	0.40	0.012

Standard:

SI25		1.82	0.053

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

21-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5568

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07091
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	E192611	1.8	1.34	<5	95	<5	3.68	1	15	88	1462	3.28	<10	0.92	984	105	0.03	6	1190	38	10	<20	249	0.03	<10	52	<10	7	64
2	E192612	0.8	1.31	20	145	<5	5.85	<1	14	73	725	3.15	<10	0.95	1533	46	0.04	4	1260	48	5	<20	264	0.04	<10	52	<10	10	57
3	E192613	1.0	1.20	15	110	<5	3.70	6	14	94	968	2.97	<10	0.83	1027	60	0.02	6	1240	252	<5	<20	178	0.03	<10	41	<10	9	267
4	E192614	0.8	1.42	10	130	<5	3.77	<1	14	60	676	3.29	<10	0.98	1132	134	0.02	4	1380	40	10	<20	164	0.04	<10	42	<10	8	63
5	E192615	0.6	1.47	10	140	<5	3.31	1	13	71	502	3.56	<10	1.03	952	40	0.03	5	1460	38	5	<20	210	0.03	<10	42	<10	6	55
6	E192616	1.1	1.40	5	120	<5	3.35	1	15	81	899	3.33	<10	0.94	872	82	0.03	5	1340	46	5	<20	234	0.03	<10	43	<10	8	68
7	E192617	1.4	1.52	20	115	<5	2.24	<1	17	62	1162	3.48	<10	1.11	658	75	0.04	5	1490	60	5	<20	174	0.04	<10	48	<10	7	74
8	E192618	<0.2	1.03	5	265	15	0.68	<1	8	80	8	2.28	<10	0.58	572	4	0.11	6	780	20	<5	<20	98	0.15	<10	48	<10	4	47
9	E192619	0.9	1.15	15	110	<5	2.03	<1	13	89	1068	2.88	<10	0.80	605	276	0.03	4	1240	46	<5	<20	140	0.03	<10	39	<10	7	68
10	E192620	0.9	1.32	20	110	<5	2.37	1	15	91	740	3.25	<10	0.88	683	145	0.03	3	1370	56	<5	<20	168	0.03	<10	49	<10	8	92
11	E192621	0.6	1.33	10	115	<5	3.70	2	15	88	581	3.31	<10	0.90	902	140	0.03	7	1350	42	10	<20	222	0.04	<10	48	<10	8	96
12	E192622	0.6	1.36	20	90	<5	3.16	<1	16	68	544	3.31	<10	0.99	833	77	0.02	4	1560	44	<5	<20	169	0.05	<10	52	<10	10	54
13	E192623	0.5	1.30	15	75	<5	2.95	<1	18	61	480	3.75	<10	0.96	812	45	0.03	5	1440	38	<5	<20	206	0.05	<10	55	<10	8	48
14	E192624	0.4	1.46	10	100	<5	2.62	<1	18	62	489	3.77	<10	1.09	765	136	0.03	5	1600	40	<5	<20	173	0.06	<10	55	<10	9	54
15	E192625	0.7	1.54	30	100	<5	2.16	<1	16	92	709	3.47	<10	1.01	635	121	0.03	5	1630	56	5	<20	132	0.03	<10	51	<10	8	76
16	E192626	0.6	1.45	10	115	<5	2.23	<1	17	67	622	3.45	<10	1.04	624	231	0.03	4	1520	36	<5	<20	167	0.04	<10	52	<10	8	48
17	E192627	0.9	1.48	15	120	<5	1.81	<1	15	64	1031	3.56	<10	1.11	604	158	0.03	5	1540	40	<5	<20	146	0.04	<10	63	<10	9	59
18	E192628	1.2	1.53	15	120	<5	2.22	<1	18	75	1116	4.03	<10	1.13	726	128	0.04	4	1480	40	<5	<20	189	0.04	<10	61	<10	9	62
19	E192629	1.4	1.48	20	125	<5	2.07	<1	16	87	886	3.81	<10	1.02	682	106	0.05	5	1440	48	5	<20	176	0.05	<10	65	<10	8	87
20	E192630	1.2	1.22	40	165	<5	1.74	<1	15	95	810	3.17	<10	0.84	596	88	0.03	5	1180	46	5	<20	173	0.08	<10	39	<10	14	51
21	E192631	1.2	1.19	40	100	<5	3.15	<1	14	87	770	3.47	<10	0.72	878	98	0.02	<1	1110	38	<5	<20	169	0.08	<10	27	<10	9	49
22	E192632	0.7	0.96	35	240	<5	2.69	<1	9	104	685	2.22	<10	0.54	544	146	0.03	5	1110	32	5	<20	237	0.08	<10	28	<10	10	33
23	E192633	0.6	1.01	25	235	<5	2.18	<1	10	93	652	2.66	<10	0.65	516	285	0.03	2	1050	30	<5	<20	220	0.09	<10	34	<10	10	39
24	E192634	0.9	0.93	20	180	<5	2.32	<1	10	83	921	2.09	<10	0.60	555	176	0.03	3	1060	30	<5	<20	187	0.09	<10	26	<10	10	37
25	E192635	3.0	1.25	35	550	<5	1.08	3	23	52	2623	3.60	20	0.61	206	214	0.04	10	580	62	10	<20	66	0.06	<10	49	<10	8	264

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	E192636	1.2	0.98	30	210	<5	2.04	<1	9	92	1077	2.12	<10	0.67	535	387	0.03	4	1080	34	<5	<20	160	0.08	<10	28	<10	11	44
27	E192637	2.1	0.84	35	130	<5	2.55	<1	16	139	1740	2.28	<10	0.51	598	278	0.03	4	920	78	<5	<20	179	0.09	<10	24	<10	18	78
28	E192638	1.5	1.00	25	145	<5	2.44	<1	12	125	1221	2.64	<10	0.61	589	223	0.03	5	960	36	<5	<20	220	0.09	<10	32	<10	9	80
29	E192639	1.3	0.90	55	95	<5	2.05	<1	11	103	1100	2.37	<10	0.59	514	718	0.03	4	970	44	<5	<20	156	0.09	<10	27	<10	9	47
30	E192640	0.8	0.94	25	165	<5	2.66	<1	12	82	906	2.22	<10	0.60	581	124	0.03	3	1130	32	<5	<20	251	0.09	<10	28	<10	11	35
31	E192641	1.4	1.04	25	180	<5	2.58	<1	14	108	1303	2.51	<10	0.60	600	174	0.04	4	1070	36	5	<20	285	0.10	<10	33	<10	10	46
32	E192642	1.6	1.09	30	155	<5	2.42	<1	12	74	1070	2.44	<10	0.64	649	168	0.02	3	1170	44	5	<20	156	0.07	<10	26	<10	11	74
33	E192643	1.2	1.13	25	175	<5	2.39	<1	10	83	773	2.42	<10	0.69	688	125	0.02	6	1160	44	15	<20	130	0.05	<10	25	<10	11	62
34	E192644	1.2	1.03	25	155	<5	3.31	<1	9	69	801	1.96	<10	0.58	960	299	<0.01	3	1120	44	5	<20	140	0.05	<10	21	<10	9	57
35	E192645	5.3	0.99	35	80	<5	3.93	4	14	84	1965	2.84	<10	0.57	1148	214	0.01	5	1080	284	<5	<20	181	0.05	<10	22	<10	9	298
QC DATA:																													
Repeat:																													
1	E192611	1.8	1.28	5	85	<5	3.64	<1	15	85	1441	3.22	<10	0.91	974	96	0.03	5	1210	44	10	<20	256	0.03	<10	49	<10	9	63
10	E192620	0.8	1.29	20	100	<5	2.38	1	15	87	733	3.24	<10	0.87	682	138	0.03	4	1400	60	<5	<20	165	0.03	<10	48	<10	8	93
19	E192629	1.4	1.42	30	115	<5	2.10	<1	17	86	879	3.83	<10	1.00	688	104	0.04	6	1480	50	<5	<20	178	0.05	<10	63	<10	8	90
Resplit:																													
1	E192611	1.8	1.35	20	105	<5	3.48	<1	14	92	1509	3.31	<10	0.96	905	99	0.03	5	1210	40	10	<20	237	0.03	<10	51	<10	9	70
Standard:																													
Pb113		11.6	0.29	45	60	<5	1.91	40	3	7	2183	1.18	<10	0.10	1566	68	0.02	1.	90	5584	15	<20	83	0.03	<10	9	<10	<1	7024

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa/nl
dl/5568
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5569

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

18-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07092
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37551	0.43	0.013
2	G37552	0.34	0.010
3	G37553	0.48	0.014
4	G37554	0.65	0.019
5	G37555	0.55	0.016
6	G37556	0.40	0.012
7	G37557	0.33	0.010
8	G37558	0.54	0.016
9	G37559	0.38	0.011
10	G37560	0.38	0.011
11	G37561	0.58	0.017
12	G37562	0.40	0.012
13	G37563	0.29	0.008
14	G37564	0.60	0.017
15	G37565	0.26	0.008
16	G37566	<0.03	<0.001
17	G37567	0.25	0.007
18	G37568	0.08	0.002
19	G37569	<0.03	<0.001
20	G37570	<0.03	<0.001
21	G37571	<0.03	<0.001
22	G37572	0.08	0.002
23	G37573	0.28	0.008
24	G37574	0.30	0.009
25	G37575	0.20	0.006
26	G37576	0.24	0.007

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5569 18-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	G37577	0.36	0.010
28	G37578	0.33	0.010
29	G37579	0.26	0.008
30	G37580	0.37	0.011
31	G37581	0.57	0.017
32	G37582	0.26	0.008
33	G37583	0.10	0.003
34	G37584	0.13	0.004
35	G37585	<0.03	<0.001
QC DATA:			
Repeat:			
1	G37551	0.45	0.013
10	G37560	0.26	0.008
19	G37569	<0.03	<0.001
Standard:			
SI25		1.80	0.052

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

20-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5569

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07092
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37551	1.0	1.75	30	235	<5	1.82	<1	15	39	893	4.53	<10	1.32	874	42	0.03	5	1620	48	5	<20	139	0.03	<10	63	<10	6	90
2	G37552	1.3	1.73	20	110	<5	1.75	1	18	102	1270	4.79	<10	1.32	932	31	0.02	6	1500	56	<5	<20	132	0.03	<10	62	<10	6	78
3	G37553	1.5	1.49	30	200	<5	1.42	1	14	148	1497	4.69	<10	1.15	770	38	0.03	8	1290	44	5	<20	113	0.03	<10	66	<10	4	69
4	G37554	1.5	1.34	30	160	<5	1.86	<1	13	145	1304	3.96	<10	1.01	914	35	0.02	6	1240	46	5	<20	116	0.02	<10	41	<10	5	83
5	G37555	1.3	1.63	30	250	<5	3.05	<1	13	86	1291	4.51	<10	1.17	1270	31	0.03	5	1470	44	5	<20	185	0.03	<10	57	<10	6	101
6	G37556	1.6	1.12	20	135	<5	2.57	<1	13	101	1215	3.75	<10	0.83	1054	46	0.02	5	1450	50	<5	<20	133	0.03	<10	30	<10	7	107
7	G37557	1.4	1.37	25	305	<5	2.79	<1	13	96	1159	4.70	<10	0.94	1037	48	0.02	5	1470	48	<5	<20	167	0.03	<10	55	<10	5	119
8	G37558	1.6	1.30	25	335	<5	2.65	2	13	71	1277	3.99	<10	0.92	889	41	0.04	7	1370	48	15	<20	202	0.03	<10	69	<10	6	92
9	G37559	1.8	1.29	15	225	<5	2.34	2	15	86	1405	4.97	<10	0.91	851	33	0.03	6	1330	44	5	<20	151	0.03	<10	69	<10	5	101
10	G37560	1.3	1.33	25	245	<5	2.85	<1	14	102	1252	4.33	<10	0.91	997	74	0.03	5	1420	38	5	<20	172	0.03	<10	59	<10	5	104
11	G37561	1.5	1.35	30	220	<5	2.46	<1	15	62	1370	4.35	<10	0.94	911	55	0.03	6	1450	42	5	<20	174	0.03	<10	60	<10	7	115
12	G37562	1.3	1.18	40	175	<5	2.26	<1	13	111	1165	4.14	<10	0.84	796	60	0.04	5	1250	38	<5	<20	155	0.03	<10	60	<10	6	82
13	G37563	1.4	1.28	20	175	<5	3.21	<1	13	96	1218	4.25	<10	0.90	1019	38	0.03	5	1330	42	5	<20	230	0.03	<10	54	<10	7	83
14	G37564	2.4	1.31	25	155	<5	2.84	<1	16	83	2208	4.86	<10	0.95	950	54	0.03	5	1170	40	<5	<20	303	0.03	<10	73	<10	5	87
15	G37565	0.9	2.34	45	400	<5	5.05	<1	20	95	784	4.86	<10	2.14	1317	32	0.04	29	1320	64	15	<20	257	0.07	<10	92	<10	8	104
16	G37566	<0.2	4.08	60	1240	55	6.78	<1	39	151	52	6.15	<10	4.54	1870	5	0.02	88	720	100	25	<20	396	0.27	<10	144	<10	10	89
17	G37567	0.8	3.65	35	100	<5	3.39	1	40	119	563	7.53	<10	3.69	1542	47	0.02	67	1140	94	20	<20	173	0.08	<10	109	<10	5	225
18	G37568	0.2	4.07	45	875	30	6.68	<1	40	172	80	6.49	<10	4.58	2011	7	0.01	101	570	162	25	<20	415	0.15	<10	138	<10	8	296
19	G37569	<0.2	4.49	60	280	40	6.38	<1	47	197	65	6.57	<10	5.07	1627	6	0.02	103	630	110	25	<20	316	0.24	<10	154	<10	9	97
20	G37570	<0.2	4.49	50	520	55	6.52	<1	44	188	51	6.77	<10	5.02	1851	6	0.02	107	620	106	20	<20	321	0.14	<10	144	<10	9	106
21	G37571	0.5	4.34	55	180	60	5.19	<1	48	204	56	6.62	<10	4.77	1725	6	0.02	133	580	106	25	<20	258	0.13	<10	127	<10	9	106
22	G37572	0.4	3.16	50	590	10	2.98	<1	34	168	355	5.59	<10	3.19	1097	16	0.03	86	1070	82	15	<20	181	0.13	<10	106	<10	8	102
23	G37573	1.3	1.53	40	220	<5	2.43	<1	15	60	989	4.49	<10	1.14	973	42	0.04	5	1680	42	<5	<20	142	0.04	<10	69	<10	5	83
24	G37574	1.4	1.36	40	270	<5	2.56	<1	14	55	1003	3.87	<10	1.01	982	44	0.04	4	1610	40	5	<20	150	0.03	<10	69	<10	8	70
25	G37575	0.8	2.73	40	285	<5	3.92	<1	28	105	673	5.09	<10	2.69	1263	39	0.03	41	1260	82	20	<20	259	0.12	<10	94	<10	7	135

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37576	1.3	1.88	40	240	<5	3.04	<1	17	66	860	3.85	<10	1.55	1009	63	0.02	12	1660	66	10	<20	171	0.06	<10	56	<10	8	94
27	G37577	1.8	1.49	40	185	<5	2.16	<1	13	87	1325	3.20	<10	1.09	817	82	0.02	5	1630	88	10	<20	126	0.04	<10	41	<10	8	82
28	G37578	1.4	1.50	35	125	<5	3.91	<1	17	70	1142	4.14	<10	1.15	1407	63	0.03	5	1560	50	<5	<20	186	0.06	<10	55	<10	10	90
29	G37579	1.6	1.50	40	145	<5	2.19	2	18	58	1079	4.69	<10	1.10	868	58	0.04	6	1760	48	15	<20	130	0.04	<10	64	<10	7	93
30	G37580	0.9	1.17	15	135	<5	1.65	<1	17	26	4011	3.73	<10	1.09	731	7	0.17	16	1380	36	10	<20	98	0.19	<10	168	<10	8	53
31	G37581	2.3	1.48	50	95	<5	2.33	<1	18	86	1965	4.70	<10	1.09	846	79	0.05	5	1500	44	<5	<20	137	0.08	<10	67	<10	6	79
32	G37582	1.3	1.48	60	130	<5	3.04	<1	19	42	870	4.17	<10	1.11	941	47	0.03	6	1990	44	5	<20	172	0.05	<10	49	<10	9	113
33	G37583	0.9	0.60	40	55	<5	4.40	1	18	96	385	3.99	<10	0.30	851	47	0.02	6	1670	54	<5	<20	303	0.03	<10	18	<10	6	42
34	G37584	0.9	0.77	45	40	<5	2.16	<1	22	68	459	4.65	<10	0.54	457	34	0.02	5	1960	82	<5	<20	86	0.11	<10	28	<10	7	69
35	G37585	<0.2	1.30	65	200	25	0.51	<1	8	97	6	2.74	<10	0.61	549	3	0.13	9	930	22	<5	<20	103	0.18	<10	57	<10	5	44
QC DATA:																													
Repeat:																													
1	G37551	1.0	1.83	40	265	<5	1.85	<1	15	38	911	4.59	<10	1.35	886	44	0.03	6	1650	50	5	<20	148	0.03	<10	66	<10	6	90
10	G37560	1.3	1.34	35	275	<5	2.88	2	15	107	1232	4.39	<10	0.91	1007	73	0.03	7	1450	42	10	<20	187	0.03	<10	61	<10	8	106
19	G37569	<0.2	4.58	60	295	70	6.46	1	48	203	65	6.74	<10	5.13	1656	6	0.02	107	650	118	25	<20	324	0.27	<10	160	<10	10	99
Resplit:																													
1	G37551	0.9	1.78	40	230	<5	1.84	<1	15	41	895	4.69	<10	1.29	879	43	0.03	4	1640	52	<5	<20	140	0.03	<10	65	<10	6	101
Standard:																													
Pb113		11.2	0.22	45	60	<5	2.01	42	4	8	2248	1.25	<10	0.11	1538	64	0.02	2	80	5400	20	<20	87	0.02	<10	12	<10	<1	7097

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
df/5568
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5570

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

3-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07089
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37516	0.15	0.004
2	G37517	0.12	0.003
3	G37518	0.16	0.005
4	G37519	0.09	0.003
5	G37520	0.18	0.005
6	G37521	0.25	0.007
7	G37522	0.38	0.011
8	G37523	0.39	0.011
9	G37524	0.23	0.007
10	G37525	0.39	0.011
11	G37526	0.08	0.002
12	G37527	0.64	0.019
13	G37528	0.38	0.011
14	G37529	0.70	0.020
15	G37530	0.36	0.010
16	G37531	0.16	0.005
17	G37532	0.15	0.004
18	G37533	0.32	0.009
19	G37534	0.17	0.005
20	G37535	<0.03	<0.001
21	G37536	0.25	0.007
22	G37537	0.18	0.005
23	G37538	0.25	0.007
24	G37539	0.51	0.015
25	G37540	0.15	0.004
26	G37541	0.18	0.005
27	G37542	0.30	0.009
28	G37543	0.19	0.006

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5570 3-Oct-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G37544	0.20	0.006
30	G37545	0.30	0.009
31	G37546	0.19	0.006
32	G37547	0.14	0.004
33	G37548	0.46	0.013
34	G37549	0.66	0.019
35	G37550	0.67	0.020
QC DATA:			
Repeat:			
1	G37516	0.14	0.004
10	G37525	0.39	0.011
12	G37527	0.69	0.020
14	G37529	0.67	0.020
18	G37533	0.38	0.011
19	G37534	0.17	0.005
Resplits:			
1	G37516	0.16	0.005
Standard:			
SI25		1.79	0.052

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

1-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5570

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07089
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37516	0.7	0.73	10	270	<5	2.02	<1	7	65	542	2.26	<10	0.44	654	31	0.02	3	1030	16	<5	<20	124	0.05	<10	21	<10	7	47
2	G37517	0.6	0.84	15	150	<5	2.51	<1	8	97	405	2.66	<10	0.52	878	41	0.02	4	1000	46	<5	<20	152	0.05	<10	22	<10	7	59
3	G37518	0.7	0.73	5	420	<5	2.74	1	7	94	576	2.49	<10	0.43	804	24	0.03	4	1040	14	<5	<20	223	0.06	<10	31	<10	8	41
4	G37519	0.5	0.76	10	360	<5	2.75	<1	8	78	362	2.57	<10	0.43	836	29	0.02	4	1080	12	<5	<20	182	0.06	<10	29	<10	7	45
5	G37520	0.7	0.82	15	160	<5	2.61	<1	9	91	444	2.95	<10	0.47	839	28	0.02	3	1000	12	<5	<20	150	0.05	<10	24	<10	7	45
6	G37521	1.4	0.90	10	175	<5	2.16	<1	8	145	1114	2.66	<10	0.52	737	69	0.02	4	890	20	<5	<20	131	0.06	<10	22	<10	7	47
7	G37522	1.5	1.06	15	125	<5	2.43	1	10	106	1262	3.32	<10	0.69	883	44	0.01	4	1000	12	<5	<20	134	0.06	<10	25	<10	7	51
8	G37523	1.4	0.96	15	160	<5	1.94	<1	7	132	1540	2.31	<10	0.61	676	62	0.02	5	980	14	<5	<20	119	0.06	<10	20	<10	7	40
9	G37524	0.9	0.86	10	260	<5	2.51	<1	7	105	761	2.86	<10	0.55	847	61	0.03	4	990	20	<5	<20	176	0.07	<10	29	<10	8	61
10	G37525	1.3	1.00	15	150	<5	1.65	1	8	131	1368	2.74	<10	0.66	640	174	0.02	4	970	18	<5	<20	114	0.06	<10	25	<10	6	53
11	G37526	0.2	0.99	110	145	35	0.28	4	66	250	464	>10	20	0.24	528	104	0.05	443	150	116	5	<20	24	0.01	<10	20	<10	6	393
12	G37527	1.8	0.86	10	135	<5	1.56	<1	5	150	1871	2.01	<10	0.58	460	227	0.02	6	840	16	<5	<20	100	0.06	<10	20	<10	7	39
13	G37528	1.7	0.44	5	100	<5	2.07	<1	7	176	2022	1.25	<10	0.23	403	64	0.01	6	500	22	<5	<20	114	0.04	<10	8	<10	6	17
14	G37529	2.4	0.89	10	125	<5	2.56	<1	7	124	2576	2.22	<10	0.54	637	51	0.01	4	950	12	<5	<20	163	0.06	<10	22	<10	7	37
15	G37530	1.3	0.86	15	140	<5	2.95	<1	7	124	1264	2.42	<10	0.49	840	71	<0.01	4	930	12	<5	<20	159	0.04	<10	16	<10	7	42
16	G37531	0.7	0.79	10	195	<5	2.88	<1	7	83	794	2.51	<10	0.43	747	42	0.02	3	1020	14	<5	<20	171	0.06	<10	22	<10	7	37
17	G37532	0.6	0.87	15	205	<5	2.79	<1	9	92	537	2.90	<10	0.47	761	41	0.03	4	1080	8	<5	<20	235	0.07	<10	27	<10	7	43
18	G37533	0.9	0.87	10	140	<5	2.47	<1	9	98	780	2.55	<10	0.50	775	57	0.03	4	1050	40	<5	<20	208	0.07	<10	24	<10	8	45
19	G37534	0.8	0.85	10	180	<5	2.66	<1	8	120	743	2.46	<10	0.45	938	42	0.02	4	1050	14	<5	<20	173	0.05	<10	20	<10	8	49
20	G37535	<0.2	1.03	10	265	<5	0.64	<1	7	97	3	2.19	<10	0.53	568	2	0.09	6	870	10	<5	<20	90	0.13	<10	40	<10	4	51
21	G37536	0.8	0.89	10	165	<5	3.00	1	8	116	716	2.75	<10	0.54	1136	55	0.02	4	950	20	<5	<20	211	0.05	<10	20	<10	6	59
22	G37537	0.8	0.84	10	160	<5	2.96	<1	9	103	808	2.42	<10	0.50	998	72	0.01	4	1010	14	<5	<20	181	0.05	<10	18	<10	8	50
23	G37538	1.0	0.99	15	130	<5	2.96	1	11	124	916	3.08	<10	0.55	1099	32	0.01	4	1000	12	<5	<20	170	0.06	<10	20	<10	7	60
24	G37539	2.2	0.76	10	130	<5	2.69	<1	7	165	2189	1.81	<10	0.42	790	177	<0.01	5	800	26	<5	<20	167	0.06	<10	14	<10	6	40
25	G37540	0.7	0.88	10	240	<5	2.67	1	9	108	513	3.45	<10	0.50	1057	27	0.02	4	1020	24	<5	<20	214	0.07	<10	30	<10	7	74

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37541	0.8	0.87	10	230	<5	2.51	1	10	108	766	3.59	<10	0.51	1014	60	0.02	3	1030	18	<5	<20	189	0.07	<10	28	<10	7	62
27	G37542	1.3	0.79	15	130	<5	2.04	1	8	97	896	3.00	<10	0.45	1035	55	0.02	4	650	24	<5	<20	126	0.06	<10	39	<10	6	56
28	G37543	0.6	0.38	10	45	<5	2.92	1	14	78	583	3.54	<10	0.74	912	36	0.01	3	1600	12	<5	<20	113	<0.01	<10	10	<10	6	37
29	G37544	0.8	0.35	10	45	<5	2.78	1	13	70	608	2.98	<10	0.71	782	42	0.01	3	1430	14	<5	<20	146	<0.01	<10	9	<10	6	31
30	G37545	0.9	0.52	15	55	<5	2.41	1	14	76	770	3.28	<10	0.83	739	84	0.01	3	1500	12	<5	<20	93	<0.01	<10	13	<10	6	45
31	G37546	1.1	0.96	20	45	<5	2.05	1	14	88	840	3.61	<10	0.94	742	62	0.02	5	1480	16	<5	<20	103	<0.01	<10	26	<10	6	54
32	G37547	0.7	2.14	30	70	<5	2.28	1	14	142	611	3.95	<10	2.69	1369	65	0.02	18	1050	34	<5	<20	138	<0.01	<10	41	<10	6	120
33	G37548	2.0	1.72	30	105	<5	3.04	1	10	116	1781	3.68	<10	1.48	1333	44	<0.01	5	1420	18	<5	<20	158	<0.01	<10	34	<10	7	77
34	G37549	1.9	1.79	20	145	<5	1.03	1	10	104	1957	3.73	<10	1.43	784	36	<0.01	4	1700	14	<5	<20	64	<0.01	<10	36	<10	7	70
35	G37550	1.7	1.41	25	95	<5	2.00	1	11	101	1675	3.44	<10	1.03	979	28	<0.01	5	1550	18	<5	<20	128	<0.01	<10	27	<10	7	60
QC DATA:																													
Repeat:																													
1	G37516	0.6	0.76	10	300	<5	1.99	<1	7	67	544	2.27	<10	0.44	656	30	0.02	4	1030	18	<5	<20	125	0.05	<10	22	<10	7	48
10	G37525	1.4	1.03	10	170	<5	1.72	1	8	140	1392	2.84	<10	0.67	660	185	0.02	5	990	18	<5	<20	118	0.07	<10	25	<10	7	54
19	G37534	0.9	0.84	10	190	<5	2.74	1	9	126	753	2.48	<10	0.44	975	48	0.02	5	1040	14	<5	<20	179	0.06	<10	19	<10	8	53
Resplit:																													
1	G37516	0.8	0.83	10	275	<5	2.06	<1	8	64	545	2.22	<10	0.44	633	31	0.02	4	1100	20	<5	<20	126	0.05	<10	24	<10	8	53
Standard:																													
Pb113		10.9	0.27	40	60	<5	1.96	48	2	2	2331	1.14	<10	0.10	1523	62	0.01	1	90	5612	5	<20	77	0.01	<10	6	<10	1	7065

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/n5570S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5571

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

25-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07093
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	E192646	0.25	0.007
2	E192647	0.29	0.008
3	E192648	0.35	0.010
4	E192649	0.35	0.010
5	E192650	0.43	0.013
6	E192651	0.38	0.011
7	E192652	0.25	0.007
8	E192653	0.35	0.010
9	E192654	0.24	0.007
10	E192655	0.52	0.015
11	E192656	0.35	0.010
12	E192657	0.60	0.017
13	E192658	0.41	0.012
14	E192659	0.32	0.009
15	E192660	<0.03	<0.001
16	E192661	0.86	0.025
17	E192662	0.50	0.015
18	E192663	0.36	0.010
19	E192664	0.16	0.005
20	E192665	0.20	0.006
21	E192666	0.25	0.007
22	E192667	0.09	0.003
23	E192668	0.18	0.005
24	E192669	0.19	0.006
25	E192670	0.22	0.006
26	E192671	0.13	0.004
27	E192672	0.16	0.005
28	E192673	0.06	<0.001

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 25-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	E192674	0.06	0.002
30	E192675	0.13	0.004
31	E192676	1.01	0.029
32	E192677	0.13	0.004
33	E192678	0.30	0.009
34	E192679	0.16	0.005
35	E192680	0.11	0.003
QC DATA:			
Repeat:			
1	E192646	0.23	0.007
10	E192655	0.48	0.014
16	E192661	0.85	0.025
19	E192664	0.16	0.005
Resplits:			
1	E192646	0.29	0.008
Standard:			
SI25		1.82	0.053

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

1-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5571

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07093
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	E192646	0.8	0.91	10	115	<5	1.78	<1	5	33	835	1.35	<10	0.65	476	139	0.03	3	850	10	<5	<20	101	0.04	<10	10	<10	7	29
2	E192647	1.3	0.96	10	80	<5	1.23	<1	8	38	1111	1.54	<10	0.69	319	225	0.04	3	830	22	<5	<20	84	0.05	<10	15	<10	7	70
3	E192648	1.4	0.95	10	85	<5	1.29	<1	7	33	1311	1.42	<10	0.64	321	97	0.03	3	870	12	<5	<20	92	0.05	<10	14	<10	8	25
4	E192649	1.2	0.96	10	115	<5	1.40	<1	6	34	1332	1.39	<10	0.69	357	141	0.03	3	880	7	<5	<20	94	0.03	<10	13	<10	7	24
5	E192650	2.0	0.79	15	65	<5	1.86	<1	6	39	1437	1.22	<10	0.53	581	172	0.02	3	780	12	<5	<20	89	0.01	<10	10	<10	6	25
6	E192651	2.2	0.78	15	60	<5	1.47	<1	7	39	1368	1.45	<10	0.49	481	97	0.02	3	860	14	<5	<20	73	0.02	<10	9	<10	7	24
7	E192652	1.0	0.86	10	70	<5	1.61	<1	6	29	886	1.28	<10	0.65	482	82	0.02	3	830	7	<5	<20	94	0.02	<10	10	<10	7	27
8	E192653	1.0	0.65	10	50	<5	2.03	<1	6	50	818	1.14	<10	0.43	512	248	0.02	3	620	10	<5	<20	108	0.02	<10	7	<10	6	25
9	E192654	1.1	0.83	10	95	<5	1.60	<1	6	64	1003	1.40	<10	0.53	431	104	0.03	4	840	10	<5	<20	97	0.02	<10	11	<10	6	24
10	E192655	2.3	0.80	10	80	<5	1.35	<1	5	56	1450	1.25	<10	0.55	370	115	0.03	4	820	7	<5	<20	72	0.02	<10	9	<10	7	21
11	E192656	3.0	0.82	15	85	<5	1.03	<1	5	52	938	1.17	<10	0.51	330	304	0.02	3	830	7	<5	<20	57	0.01	<10	9	<10	6	21
12	E192657	3.2	0.84	35	55	<5	1.69	<1	5	87	1147	1.52	<10	0.56	488	95	0.02	4	720	10	<5	<20	69	0.01	<10	9	<10	5	22
13	E192658	2.4	0.89	10	80	<5	1.66	<1	7	42	1323	1.35	<10	0.61	455	82	0.02	3	790	10	<5	<20	76	0.01	<10	9	<10	6	27
14	E192659	5.7	0.75	15	125	<5	2.19	<1	6	53	1342	1.28	<10	0.52	546	116	0.02	3	830	14	<5	<20	102	0.01	<10	8	<10	6	27
15	E192660	<0.2	1.13	10	225	<5	0.40	<1	5	81	6	1.97	<10	0.66	345	2	0.20	6	710	10	<5	<20	73	0.10	<10	39	<10	4	37
16	E192661	3.9	0.94	40	35	<5	1.59	<1	8	44	1098	2.09	<10	0.64	475	103	0.02	3	1130	26	<5	<20	69	0.02	<10	15	<10	5	52
17	E192662	6.6	0.81	25	35	<5	1.95	<1	9	55	1280	1.68	<10	0.59	653	112	0.02	4	1150	41	<5	<20	87	0.02	<10	12	<10	6	52
18	E192663	7.5	0.80	15	40	<5	1.27	2	9	62	1306	1.96	<10	0.62	451	113	0.03	4	1060	166	<5	<20	61	0.05	<10	13	<10	7	63
19	E192664	1.2	0.91	10	65	<5	1.29	<1	9	59	908	1.66	<10	0.74	328	189	0.03	4	960	12	<5	<20	102	0.07	<10	14	<10	8	39
20	E192665	1.1	0.81	10	40	<5	1.04	<1	11	44	1359	1.74	<10	0.63	242	68	0.03	4	1070	14	<5	<20	44	0.09	<10	19	<10	9	28
21	E192666	0.5	1.03	10	35	<5	1.86	<1	10	39	737	2.25	<10	0.98	402	44	0.04	4	1270	10	<5	<20	60	0.09	<10	31	<10	8	31
22	E192667	0.7	1.17	15	35	<5	1.55	<1	12	38	702	2.85	<10	1.06	358	43	0.05	3	1350	14	<5	<20	63	0.08	<10	37	<10	8	34
23	E192668	0.6	0.95	15	35	<5	2.45	<1	11	25	853	2.13	<10	0.88	287	59	0.03	3	1340	12	<5	<20	193	0.12	<10	34	<10	8	28
24	E192669	1.3	0.91	10	30	<5	2.39	<1	11	44	1387	2.19	<10	0.79	297	145	0.03	3	1400	22	<5	<20	202	0.09	<10	27	<10	9	29
25	E192670	1.4	0.88	10	30	<5	2.46	<1	11	38	1489	2.19	<10	0.81	308	192	0.03	3	1410	19	<5	<20	200	0.09	<10	29	<10	9	29

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	E192671	0.9	1.01	15	30	<5	1.98	<1	12	40	1232	2.26	<10	0.93	344	246	0.03	3	1450	19	<5	<20	140	0.10	<10	34	<10	9	46
27	E192672	0.7	0.91	15	30	<5	1.77	<1	12	51	1067	2.46	<10	0.70	379	57	0.02	3	1350	14	<5	<20	67	0.07	<10	22	<10	9	29
28	E192673	0.6	1.31	20	35	<5	2.19	<1	16	43	660	3.20	<10	1.17	686	95	0.03	3	1290	14	<5	<20	96	0.14	<10	38	<10	9	67
29	E192674	<0.2	2.38	60	95	10	2.69	1	20	47	31	4.78	<10	2.32	1444	3	0.03	5	940	48	<5	<20	103	0.16	<10	98	<10	11	111
30	E192675	0.5	1.17	45	45	<5	1.29	<1	11	81	126	2.93	<10	1.34	726	7	0.09	20	1140	19	<5	<20	76	0.10	<10	71	<10	7	43
31	E192676	3.7	1.15	60	55	<5	0.69	2	12	49	3269	3.83	20	0.54	215	197	0.04	15	410	124	35	<20	33	0.03	<10	42	<10	8	151
32	E192677	1.1	0.97	20	35	<5	1.55	<1	12	70	72	2.51	<10	1.19	728	2	0.08	19	1120	12	<5	<20	101	0.09	<10	66	<10	7	45
33	E192678	1.4	0.93	20	40	5	1.55	<1	10	86	44	3.02	<10	1.26	823	5	0.08	16	970	60	<5	<20	108	0.10	<10	77	<10	8	64
34	E192679	1.0	1.07	25	40	<5	1.57	<1	14	57	59	2.47	<10	1.25	918	3	0.05	17	1030	26	<5	<20	110	0.10	<10	56	<10	7	59
35	E192680	0.6	0.88	15	40	<5	2.32	<1	8	72	50	3.05	<10	1.28	958	7	0.10	13	690	26	<5	<20	177	0.06	<10	69	<10	5	48
QC DATA:																													
Repeat:																													
1	E192646	0.9	0.85	10	110	<5	1.74	<1	5	33	838	1.38	<10	0.64	480	127	0.02	3	850	10	<5	<20	104	0.03	<10	10	<10	7	29
10	E192655	2.0	0.76	10	80	<5	1.51	<1	5	58	1474	1.32	<10	0.52	376	119	0.02	4	860	10	<5	<20	78	0.02	<10	8	<10	7	24
19	E192664	1.2	0.86	10	55	<5	1.32	<1	10	62	906	1.64	<10	0.71	370	204	0.02	4	1020	12	<5	<20	98	0.07	<10	15	<10	8	42
Resplit:																													
1	E192646	0.8	0.83	10	110	<5	1.79	<1	6	56	902	1.38	<10	0.57	515	138	0.02	4	950	10	<5	<20	104	0.04	<10	11	<10	8	29
Standard:																													
Pb113		11.0	0.27	40	55	<5	1.60	37	2	<1	2317	1.00	<10	0.11	1437	67	0.02	1	90	5400	5	<20	81	<0.01	<10	4	<10	1	6878

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa/nl
df/n5571
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5572

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

9-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07094
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37586	0.07	0.002
2	G37587	0.13	0.004
3	G37588	0.08	0.002
4	G37589	0.08	0.002
5	G37590	0.08	0.002
6	G37591	0.07	0.002
7	G37592	0.11	0.003
8	G37593	0.10	0.003
9	G37594	0.06	0.002
10	G37595	0.05	0.001
11	G37596	0.13	0.004
12	G37597	0.16	0.005
13	G37598	0.08	0.002
14	G37599	0.10	0.003
15	G37600	<0.03	<0.001
16	G37601	1.05	0.031
17	G37602	0.11	0.003
18	G37603	0.06	0.002
19	G37604	0.07	0.002
20	G37605	0.08	0.002
21	G37606	0.12	0.003
22	G37607	0.08	0.002
23	G37608	0.12	0.003
24	G37609	0.04	0.001
25	G37610	0.05	0.001
26	G37611	0.06	0.002
27	G37612	0.07	0.002
28	G37613	0.11	0.003

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5572 9-Oct-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G37614	0.17	0.005
30	G37615	0.19	0.006
31	G37616	0.13	0.004
32	G37617	0.21	0.006
33	G37618	0.13	0.004
34	G37619	0.12	0.003
35	G37620	0.08	0.002
QC DATA:			
Repeat:			
1	G37586	0.07	0.002
10	G37595	0.06	0.002
19	G37604	0.07	0.002
Resplits:			
1	G37586	0.07	0.002
Standard:			
OXI54		1.86	0.054

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

1-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5572

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07094
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37586	0.7	0.74	<5	40	<5	1.26	1	20	79	352	4.10	<10	0.58	292	14	0.03	9	1620	40	10	<20	63	0.09	<10	29	<10	7	49
2	G37587	0.4	0.79	<5	40	<5	1.82	3	16	64	337	3.79	<10	0.71	437	14	0.03	11	1560	38	25	<20	68	0.06	<10	34	<10	6	78
3	G37588	0.5	0.72	<5	40	<5	1.59	<1	16	83	280	3.83	<10	0.56	378	10	0.02	7	1680	46	10	<20	55	0.09	<10	26	<10	7	38
4	G37589	0.2	0.75	<5	45	15	1.63	1	15	69	174	3.78	<10	0.70	425	12	0.02	7	1620	38	10	<20	85	0.09	<10	36	<10	7	44
5	G37590	0.2	0.91	<5	45	5	1.66	2	16	79	153	4.06	<10	0.94	481	7	0.03	9	1650	32	20	<20	79	0.09	<10	46	<10	6	56
6	G37591	0.3	0.89	<5	45	15	1.52	1	17	93	162	4.07	<10	0.85	431	8	0.03	7	1640	34	10	<20	66	0.09	<10	42	<10	7	51
7	G37592	0.4	0.81	<5	45	<5	1.39	<1	18	105	229	4.46	<10	0.69	366	9	0.02	8	1660	36	10	<20	70	0.09	<10	37	<10	6	47
8	G37593	0.3	0.61	<5	40	5	1.63	1	18	85	149	4.36	<10	0.44	378	7	0.02	7	1450	42	10	<20	65	0.08	<10	27	<10	4	38
9	G37594	0.4	0.63	<5	45	<5	1.34	1	19	71	100	4.45	<10	0.49	329	7	0.03	8	1650	42	10	<20	72	0.09	<10	36	<10	5	37
10	G37595	0.4	0.66	<5	45	20	1.60	2	19	75	170	5.03	<10	0.49	401	9	0.02	10	1640	58	15	<20	69	0.08	<10	29	<10	5	39
11	G37596	0.4	0.84	<5	50	10	1.70	1	17	58	183	4.37	<10	0.78	485	10	0.03	7	1600	40	20	<20	92	0.09	<10	47	<10	7	61
12	G37597	0.3	0.86	<5	45	5	1.59	2	17	86	178	4.44	<10	0.81	454	9	0.03	9	1600	52	15	<20	90	0.09	<10	46	<10	6	60
13	G37598	0.2	0.82	<5	45	20	2.99	2	15	76	116	4.14	<10	0.74	645	9	0.02	10	1660	40	20	<20	101	0.08	<10	43	<10	6	47
14	G37599	0.2	0.70	<5	40	20	1.64	2	17	83	131	4.31	<10	0.60	413	11	0.02	11	1700	46	20	<20	78	0.10	<10	31	<10	5	45
15	G37600	<0.2	1.10	10	275	15	0.69	<1	7	88	5	2.25	<10	0.59	556	3	0.09	6	850	22	<5	<20	81	0.13	<10	48	<10	5	45
16	G37601	3.1	1.11	55	80	<5	0.73	3	17	61	3254	3.90	20	0.49	271	213	0.02	14	410	144	45	<20	39	0.03	<10	42	<10	7	160
17	G37602	0.4	0.57	5	50	<5	1.41	6	18	67	298	4.43	<10	0.40	380	11	<0.01	8	1700	58	20	<20	68	0.05	<10	16	<10	3	172
18	G37603	0.8	0.64	10	40	10	2.23	2	15	80	122	4.60	<10	0.57	750	13	0.01	7	1610	72	35	<20	81	0.07	<10	26	<10	3	65
19	G37604	1.8	0.63	25	45	10	1.08	2	17	72	114	5.26	<10	0.31	393	7	<0.01	7	1760	76	50	<20	65	0.05	<10	14	<10	4	53
20	G37605	3.4	0.41	20	45	20	0.76	3	17	111	113	5.37	<10	0.11	413	10	<0.01	8	1670	132	50	<20	50	0.04	<10	10	<10	3	176
21	G37606	2.6	0.29	<5	55	25	0.64	4	14	154	111	6.58	<10	<0.01	344	9	<0.01	13	1080	134	40	<20	124	0.04	<10	7	<10	1	85
22	G37607	1.5	0.49	10	45	20	0.90	3	16	133	53	5.84	<10	0.20	610	10	<0.01	13	1490	110	25	<20	86	0.06	<10	14	<10	3	62
23	G37608	0.3	1.13	20	55	<5	2.97	<1	21	99	296	3.26	<10	1.03	1338	6	<0.01	88	1310	30	25	<20	154	0.12	<10	25	<10	9	89
24	G37609	0.3	0.80	15	50	<5	1.59	1	11	133	193	3.25	<10	0.82	764	9	0.04	30	550	42	25	<20	108	0.08	<10	25	<10	4	52
25	G37610	0.4	0.55	<5	45	5	1.42	1	10	99	135	2.91	<10	0.44	661	7	0.03	28	630	42	15	<20	112	0.07	<10	23	<10	3	35

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37611	0.6	0.34	<5	35	<5	1.12	<1	11	111	223	2.21	<10	0.18	518	5	0.03	17	520	46	5	<20	197	0.05	<10	8	<10	3	31
27	G37612	1.1	0.45	<5	40	<5	0.88	4	9	138	300	2.98	<10	0.29	463	6	0.02	20	730	72	<5	<20	114	0.06	<10	13	<10	3	121
28	G37613	1.4	0.72	10	45	<5	1.31	2	11	145	289	3.21	<10	0.71	851	7	0.03	44	820	50	25	<20	106	0.06	<10	27	<10	3	70
29	G37614	1.6	0.57	5	45	<5	1.85	<1	17	155	348	3.08	<10	0.42	881	4	0.02	41	820	42	10	<20	142	0.06	<10	18	<10	4	37
30	G37615	1.6	0.55	<5	45	10	0.57	2	16	105	302	3.99	<10	0.37	293	8	0.01	48	990	48	15	<20	56	0.07	<10	14	<10	4	30
31	G37616	1.0	0.67	10	40	<5	1.47	<1	17	89	596	3.57	<10	0.55	657	3	0.02	20	870	30	<5	<20	98	0.09	<10	15	<10	3	31
32	G37617	1.0	1.30	10	55	<5	2.46	1	23	63	356	4.55	<10	1.17	1243	6	0.01	33	1650	32	15	<20	149	0.11	<10	29	<10	5	72
33	G37618	0.4	1.34	15	75	<5	1.82	<1	18	64	230	3.21	<10	1.13	997	4	0.01	37	1740	34	15	<20	122	0.10	<10	22	<10	7	63
34	G37619	0.5	1.22	10	70	10	1.83	1	23	64	121	3.70	<10	1.00	957	6	0.01	30	1440	38	15	<20	117	0.09	<10	20	<10	7	51
35	G37620	0.6	1.15	15	60	<5	1.89	<1	18	84	288	3.04	<10	0.85	1070	6	0.02	31	1180	30	20	<20	129	0.09	<10	22	<10	6	58
QC DATA:																													
Repeat:																													
1	G37586	0.6	0.68	5	45	<5	1.24	<1	20	76	351	4.08	<10	0.55	289	13	0.03	9	1620	38	10	<20	61	0.08	<10	27	<10	6	47
10	G37595	0.3	0.61	<5	50	5	1.63	<1	20	74	172	5.18	<10	0.47	404	7	0.02	9	1720	64	10	<20	67	0.07	<10	27	<10	5	40
19	G37604	1.7	0.58	15	40	25	1.06	3	17	69	112	5.16	<10	0.30	385	9	<0.01	9	1760	74	55	<20	61	0.05	10	12	<10	4	52
Resplit:																													
1	G37586	0.7	0.72	<5	45	5	1.17	2	21	87	344	4.16	<10	0.56	273	14	0.03	10	1690	48	15	<20	60	0.08	<10	28	<10	6	50
Standard:																													
Till-3		1.4	0.26	45	55	<5	1.69	39	2	7	2220	1.05	<10	0.11	1476	66	0.01	7	100	5530	20	<20	89	<0.01	<10	10	<10	<1	6898

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/7338S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5573

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

25-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07095
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35301	0.29	0.008
2	G35302	0.39	0.011
3	G35303	1.21	0.035
4	G35304	0.60	0.017
5	G35305	0.35	0.010
6	G35306	0.31	0.009
7	G35307	0.29	0.008
8	G35308	1.05	0.031
9	G35309	0.34	0.010
10	G35310	0.30	0.009
11	G35311	0.19	0.006
12	G35312	0.14	0.004
13	G35313	0.05	0.001
14	G35314	0.20	0.006
15	G35315	0.35	0.010
16	G35316	0.31	0.009
17	G35317	0.37	0.011
18	G35318	0.25	0.007
19	G35319	0.26	0.008
20	G35320	0.32	0.009
21	G35321	1.08	0.031
22	G35322	0.48	0.014
23	G35323	0.40	0.012
24	G35324	0.32	0.009
25	G35325	0.48	0.014
26	G35326	0.09	0.003
27	G35327	<0.03	<0.001

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5573 25-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G35328	0.31	0.009
29	G35329	0.33	0.010
30	G35330	0.27	0.008
31	G35331	0.18	0.005
32	G35332	0.13	0.004
33	G35333	0.17	0.005
34	G35334	0.16	0.005
35	G35335	0.14	0.004
QC DATA:			
Repeat:			
1	G35301	0.27	0.008
3	G35303	1.18	0.034
10	G35310	0.30	0.009
19	G35319	0.21	0.006
21	G35321	1.05	0.031
Resplits:			
1	G35301	0.29	0.008
Standard:			
SI25		1.86	0.054

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

1-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5573

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07095
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35301	1.5	0.86	15	35	<5	1.76	<1	6	77	668	3.57	<10	0.66	1256	2	0.02	3	970	36	<5	<20	110	0.04	<10	34	<10	6	54
2	G35302	3.1	1.05	35	35	<5	2.06	1	8	51	1175	4.33	<10	0.84	1601	1	0.02	5	1440	88	<5	<20	115	0.05	<10	48	<10	8	87
3	G35303	7.6	0.70	85	30	15	1.27	5	10	50	573	5.52	<10	0.47	982	2	0.02	5	1560	368	<5	<20	80	0.02	<10	30	<10	7	400
4	G35304	2.4	1.02	35	30	<5	1.95	<1	9	58	1185	3.96	<10	0.87	1360	2	0.02	5	1340	26	<5	<20	151	0.04	<10	42	<10	8	75
5	G35305	1.5	0.89	25	40	<5	1.94	<1	6	37	460	2.10	10	0.70	913	3	0.04	6	1780	18	<5	<20	119	0.03	<10	36	<10	9	49
6	G35306	2.4	0.93	25	30	<5	1.97	<1	8	45	801	3.34	<10	0.74	995	5	0.03	7	1810	14	<5	<20	152	0.03	<10	38	<10	10	51
7	G35307	1.3	0.98	15	50	<5	2.75	3	7	35	660	2.67	<10	0.76	1269	<1	0.04	5	1830	8	<5	<20	167	0.07	<10	36	<10	9	134
8	G35308	3.7	1.15	60	55	<5	0.74	3	13	54	3273	3.66	20	0.52	261	201	0.03	16	580	112	30	<20	39	0.03	<10	32	<10	8	134
9	G35309	2.1	1.24	15	45	<5	2.84	1	8	35	1033	2.93	<10	0.91	1334	<1	0.04	5	1760	16	<5	<20	133	0.10	<10	43	<10	10	86
10	G35310	2.6	1.26	15	45	<5	3.33	<1	9	38	1177	3.61	<10	1.01	1524	1	0.04	5	1730	20	<5	<20	157	0.10	<10	55	<10	9	80
11	G35311	2.0	0.94	15	115	<5	3.36	<1	8	41	1564	3.61	<10	0.70	1387	<1	0.05	4	1750	14	<5	<20	148	0.09	<10	65	<10	8	58
12	G35312	1.4	0.86	10	225	<5	3.35	<1	6	36	1393	3.41	<10	0.64	1295	<1	0.05	4	1680	14	<5	<20	167	0.08	<10	64	<10	7	53
13	G35313	0.9	0.39	10	95	<5	4.55	<1	2	20	487	0.67	<10	0.05	1555	2	0.03	4	1240	12	<5	<20	128	0.02	<10	5	<10	9	3
14	G35314	2.1	0.57	15	45	<5	1.35	<1	6	29	1165	1.97	<10	0.21	480	2	0.03	4	1590	12	<5	<20	64	0.01	<10	15	<10	6	21
15	G35315	1.9	1.13	20	70	<5	2.41	<1	7	38	1419	2.66	<10	0.76	1004	<1	0.04	5	1860	12	<5	<20	126	0.08	<10	51	<10	10	43
16	G35316	1.7	1.13	15	60	<5	2.19	<1	7	48	1108	2.95	<10	0.85	1152	<1	0.04	5	1820	14	<5	<20	94	0.09	<10	46	<10	9	61
17	G35317	1.6	1.14	15	50	<5	2.72	<1	8	36	926	3.04	<10	0.78	1160	<1	0.04	5	1890	18	<5	<20	88	0.09	<10	47	<10	9	82
18	G35318	1.6	1.03	15	55	<5	2.54	<1	8	38	942	3.03	<10	0.77	1180	<1	0.04	6	1920	16	<5	<20	91	0.09	<10	49	<10	9	87
19	G35319	1.4	0.91	10	345	<5	2.89	<1	7	47	1366	3.67	<10	0.65	1025	<1	0.04	4	1610	20	<5	<20	103	0.09	<10	66	<10	9	59
20	G35320	1.6	1.02	15	165	<5	3.05	<1	9	49	1570	3.77	<10	0.70	1098	<1	0.04	4	1770	22	<5	<20	104	0.09	<10	65	<10	9	66
21	G35321	1.7	0.99	15	60	<5	3.13	1	7	26	927	3.97	10	0.77	1231	<1	0.04	4	1650	18	<5	<20	122	0.08	<10	57	<10	10	89
22	G35322	2.9	0.96	20	35	<5	3.99	1	9	46	915	4.25	<10	0.69	1788	2	0.03	6	1670	42	<5	<20	130	0.08	<10	37	<10	11	114
23	G35323	1.8	0.88	20	55	<5	3.36	1	8	65	1170	3.20	<10	0.59	1441	1	0.03	5	1320	16	<5	<20	204	0.08	<10	35	<10	8	72
24	G35324	2.8	0.79	20	45	<5	4.02	<1	7	41	1324	3.98	<10	0.64	2205	1	0.02	4	1480	22	<5	<20	239	0.05	<10	35	<10	11	75
25	G35325	2.5	0.83	15	40	<5	2.52	1	9	28	938	4.26	<10	0.59	1509	1	0.02	4	1640	22	<5	<20	140	0.08	<10	43	<10	9	91

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35326	1.0	0.64	10	420	<5	2.98	<1	6	47	503	2.77	<10	0.40	1205	2	0.03	3	1170	10	<5	<20	200	0.07	<10	39	<10	8	54
27	G35327	<0.2	1.05	10	245	<5	0.65	<1	7	94	2	2.19	<10	0.61	571	1	0.09	7	940	8	<5	<20	80	0.14	<10	38	<10	5	44
28	G35328	1.1	0.85	15	60	<5	2.24	<1	7	51	847	3.90	<10	0.62	1188	<1	0.03	3	1040	14	<5	<20	129	0.05	<10	46	<10	6	55
29	G35329	1.6	0.86	15	70	<5	2.07	<1	9	62	1125	4.55	<10	0.66	1235	2	0.03	3	1070	12	<5	<20	98	0.07	<10	53	<10	6	58
30	G35330	1.8	0.65	15	90	<5	1.71	<1	7	73	1702	3.37	<10	0.44	904	3	0.03	3	750	14	<5	<20	95	0.04	<10	35	<10	5	42
31	G35331	1.3	0.70	10	275	<5	1.30	<1	5	58	1406	3.34	<10	0.44	720	2	0.04	2	760	12	<5	<20	94	0.04	<10	41	<10	5	47
32	G35332	1.0	0.67	15	260	<5	1.88	<1	6	78	816	3.14	<10	0.43	938	2	0.03	3	730	12	<5	<20	132	0.03	<10	38	<10	4	47
33	G35333	0.7	0.75	10	300	<5	1.11	<1	5	49	748	3.01	<10	0.54	664	2	0.04	3	790	10	<5	<20	93	0.04	<10	41	<10	4	46
34	G35334	1.6	0.93	15	50	<5	1.86	<1	8	83	840	3.90	<10	0.80	1050	1	0.03	15	840	16	<5	<20	97	0.06	<10	69	<10	5	64
35	G35335	1.3	0.91	10	140	<5	1.72	<1	8	103	1407	3.11	<10	0.88	937	2	0.03	14	760	14	<5	<20	116	0.08	<10	91	<10	4	55
QC DATA:																													
Repeat:																													
1	G35301	1.5	0.86	15	35	<5	1.97	<1	7	82	634	3.75	<10	0.65	1402	1	0.02	3	1010	32	<5	<20	119	0.04	<10	34	<10	6	55
10	G35310	2.6	1.11	15	40	<5	3.13	<1	9	37	1152	3.64	<10	1.01	1558	1	0.04	5	1740	20	<5	<20	158	0.09	<10	54	<10	9	84
19	G35319	1.4	0.89	10	330	<5	2.84	<1	7	46	1376	3.67	<10	0.64	1030	<1	0.04	4	1640	20	<5	<20	104	0.08	<10	64	<10	9	59
Resplit:																													
1	G35301	1.7	0.99	20	35	<5	2.14	<1	7	74	666	3.60	<10	0.62	1377	1	0.01	3	1040	38	<5	<20	109	0.04	<10	34	<10	6	61
Standard:																													
Pb113		11.9	0.32	40	60	<5	1.66	37	2	<1	2224	1.01	<10	0.11	1446	69	0.02	1	90	5488	10	<20	81	0.01	<10	4	<10	1	6998

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa/jl
df/n5571
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5574

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

3-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07096
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37621	0.13	0.004
2	G37622	0.14	0.004
3	G37623	0.15	0.004
4	G37624	0.12	0.003
5	G37625	0.19	0.006
6	G37626	0.06	0.002
7	G37627	0.18	0.005
8	G37628	0.14	0.004
9	G37629	0.25	0.007
10	G37630	0.22	0.006
11	G37631	<0.03	<0.001
12	G37632	0.42	0.012
13	G37633	0.27	0.008
14	G37634	0.17	0.005
15	G37635	0.11	0.003
16	G37636	0.12	0.003
17	G37637	0.12	0.003
18	G37638	0.11	0.003
19	G37639	0.07	0.002
20	G37640	0.08	0.002
21	G37641	0.05	0.001
22	G37642	1.85	0.054
23	G37643	0.09	0.003
24	G37644	0.08	0.002
25	G37645	0.10	0.003
26	G37646	0.06	0.002
27	G37647	0.91	0.027

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5574 3-Oct-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G37648	0.93	0.027
29	G37649	1.39	0.041
30	G37650	1.08	0.031
31	G37651	1.20	0.035
32	G37652	0.81	0.024
33	G37653	1.17	0.034
34	G37654	0.82	0.024
35	G37655	1.01	0.029
QC DATA:			
Repeat:			
1	G37621	0.13	0.004
10	G37630	0.24	0.007
19	G37639	0.07	0.002
29	G37649	1.36	0.040
31	G37651	1.29	0.038
Resplits:			
1	G37621	0.13	0.004
Standard:			
SI25		1.81	0.053

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

1-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5574

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07096
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37621	1.0	1.01	20	40	5	1.07	1	20	55	186	3.43	<10	0.73	1087	2	<0.01	35	1360	22	<5	<20	84	0.04	<10	14	<10	9	71
2	G37622	1.3	1.49	25	40	<5	0.60	1	23	80	451	4.24	<10	1.20	1304	2	<0.01	59	1370	18	<5	<20	65	0.04	<10	26	<10	9	106
3	G37623	1.2	1.48	25	45	5	0.72	1	26	72	355	4.24	<10	1.23	1331	1	<0.01	62	1330	16	<5	<20	64	0.05	<10	27	<10	9	105
4	G37624	1.7	0.93	20	35	5	0.75	1	18	86	378	4.28	<10	0.80	838	1	<0.01	50	1380	64	<5	<20	103	0.05	<10	21	<10	4	65
5	G37625	1.9	0.60	15	35	<5	1.19	<1	12	89	527	3.04	<10	0.41	870	2	0.01	24	760	30	<5	<20	137	0.06	<10	13	<10	4	44
6	G37626	0.6	0.29	5	45	<5	1.12	<1	7	103	240	1.29	<10	0.09	620	5	0.03	9	520	12	<5	<20	277	0.04	<10	7	<10	4	13
7	G37627	1.3	0.47	10	35	<5	2.42	<1	8	114	327	2.88	<10	0.35	1401	2	0.03	11	640	26	<5	<20	335	0.05	<10	14	<10	6	44
8	G37628	0.9	0.86	20	40	<5	0.98	<1	18	89	400	3.45	<10	0.75	849	2	0.03	21	990	24	<5	<20	158	0.09	<10	28	<10	7	66
9	G37629	0.5	1.16	25	45	<5	1.73	1	19	85	430	3.81	<10	0.96	1268	<1	0.02	34	1550	18	<5	<20	242	0.11	<10	28	<10	8	80
10	G37630	0.6	1.52	25	85	<5	2.18	1	19	51	401	4.41	<10	1.23	1390	<1	0.02	40	1450	20	<5	<20	299	0.09	<10	32	<10	8	68
11	G37631	<0.2	0.97	10	270	<5	0.45	<1	8	90	8	2.45	<10	0.56	604	1	0.06	7	980	18	<5	<20	95	0.16	<10	44	<10	5	40
12	G37632	0.6	1.53	20	90	<5	2.03	1	15	64	854	4.20	<10	1.29	1335	<1	0.02	28	1390	20	<5	<20	254	0.08	<10	34	<10	8	65
13	G37633	0.7	0.68	20	50	<5	1.15	1	16	83	1086	2.77	<10	0.50	682	5	0.02	26	1210	16	<5	<20	226	0.07	<10	35	<10	8	43
14	G37634	1.2	0.88	25	45	<5	1.24	2	21	74	1914	4.29	<10	0.70	973	2	0.02	29	1550	22	<5	<20	163	0.09	<10	29	<10	8	59
15	G37635	0.9	0.44	15	30	<5	0.84	2	9	99	837	3.58	<10	0.28	649	3	0.02	16	510	30	<5	<20	143	0.04	<10	16	<10	4	69
16	G37636	1.2	0.37	20	35	<5	0.78	8	13	116	558	3.70	<10	0.16	702	23	0.02	18	440	36	<5	<20	126	0.03	<10	14	<10	4	480
17	G37637	1.8	0.55	30	30	<5	0.80	3	13	103	1485	5.12	<10	0.34	721	2	0.01	32	980	48	5	<20	108	0.03	<10	19	<10	6	71
18	G37638	1.4	0.58	15	30	5	0.97	1	13	127	601	3.99	<10	0.41	988	2	0.02	39	1070	28	<5	<20	151	0.05	<10	24	<10	5	54
19	G37639	2.0	0.25	15	35	10	0.72	2	5	116	180	2.35	<10	0.03	503	1	0.02	13	590	24	<5	<20	141	0.02	<10	5	<10	4	75
20	G37640	1.0	0.35	15	40	<5	1.16	6	7	94	311	2.83	<10	0.12	1008	2	0.02	14	940	24	<5	<20	178	0.06	<10	9	<10	5	407
21	G37641	0.7	0.90	20	60	5	1.09	5	12	72	279	3.76	<10	0.78	1572	1	0.02	23	1070	20	<5	<20	165	0.08	<10	27	<10	7	328
22	G37642	4.0	1.03	40	55	<5	1.08	3	22	51	8583	4.18	20	0.61	217	615	0.02	66	340	54	20	<20	70	0.05	<10	41	<10	8	64
23	G37643	0.2	1.05	20	85	<5	1.30	<1	17	52	152	2.69	10	0.88	1259	4	0.02	39	1000	20	<5	<20	202	0.11	<10	33	<10	11	81
24	G37644	0.5	0.89	25	45	<5	1.58	2	14	79	144	3.86	10	0.81	1450	<1	0.03	22	810	82	<5	<20	294	0.12	<10	35	<10	8	119
25	G37645	0.9	1.06	25	45	5	2.95	7	14	79	257	4.32	10	1.13	2304	3	0.02	20	1170	76	<5	<20	482	0.11	<10	36	<10	9	256

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37646	0.2	1.08	25	70	<5	1.53	1	20	61	181	3.65	10	0.84	1607	1	0.02	24	830	20	<5	<20	194	0.13	<10	25	<10	9	103
27	G37647	1.5	0.21	35	25	<5	0.18	2	8	248	2625	4.47	<10	<0.01	74	55	<0.01	4	1010	26	25	<20	19	<0.01	<10	5	<10	1	73
28	G37648	1.0	0.26	15	30	<5	0.13	14	8	285	2339	4.62	<10	<0.01	73	26	<0.01	4	740	50	<5	<20	30	<0.01	<10	6	<10	1	1058
29	G37649	1.1	0.20	40	30	<5	0.14	3	8	218	1999	6.16	<10	<0.01	71	47	<0.01	2	820	82	10	<20	65	<0.01	<10	6	<10	<1	110
30	G37650	9.7	0.20	125	35	<5	0.06	3	8	265	1911	6.21	<10	<0.01	57	32	<0.01	3	340	44	65	<20	80	<0.01	<10	4	<10	2	102
31	G37651	0.8	0.18	30	30	<5	0.07	3	6	226	2210	5.31	<10	<0.01	59	142	<0.01	3	430	48	10	<20	78	<0.01	<10	4	<10	<1	107
32	G37652	1.1	0.16	15	45	<5	0.01	2	6	269	1728	5.08	<10	<0.01	58	54	<0.01	4	270	42	<5	<20	199	<0.01	<10	4	<10	<1	74
33	G37653	0.9	0.24	15	40	<5	0.16	4	9	226	2149	6.03	<10	0.02	86	63	<0.01	2	940	62	<5	<20	168	<0.01	<10	5	<10	<1	220
34	G37654	1.5	0.23	10	25	<5	0.16	6	10	214	1941	4.80	<10	<0.01	63	94	<0.01	3	930	32	<5	<20	28	<0.01	<10	4	<10	1	296
35	G37655	1.2	0.28	15	25	<5	0.18	5	11	234	1719	5.74	<10	<0.01	78	112	<0.01	3	1090	36	<5	<20	24	<0.01	<10	5	<10	1	215
QC DATA:																													
Repeat:																													
1	G37621	1.1	1.05	20	45	<5	1.14	1	22	59	183	3.61	<10	0.75	1181	2	<0.01	37	1440	22	<5	<20	90	0.04	<10	22	<10	9	69
10	G37630	0.6	1.49	25	85	<5	2.14	1	20	53	381	4.55	<10	1.21	1477	<1	0.02	41	1470	20	<5	<20	314	0.09	<10	33	<10	8	73
19	G37639	1.5	0.24	15	30	5	0.76	2	5	120	178	2.38	<10	0.02	526	1	0.02	14	610	26	<5	<20	145	0.02	<10	5	<10	4	79
Resplit:																													
1	G37621	0.8	0.90	20	40	<5	1.04	<1	21	54	180	3.37	<10	0.76	1058	3	<0.01	39	1320	22	<5	<20	84	0.04	<10	14	<10	10	68
Standard:																													
Pb113		11.2	0.24	40	60	<5	1.67	47	2	<1	2207	1.04	<10	0.09	1564	65	<0.01	2	90	5500	5	<20	87	0.01	<10	7	<10	1	7148

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/n5570S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5575

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

25-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07097
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37656	0.55	0.016
2	G37657	0.76	0.022
3	G37658	0.92	0.027
4	G37659	1.08	0.031
5	G37660	0.53	0.015
6	G37661	0.70	0.020
7	G37662	0.43	0.013
8	G37663	0.67	0.020
9	G37664	0.52	0.015
10	G37665	0.45	0.013
11	G37666	0.28	0.008
12	G37667	0.63	0.018
13	G37668	0.34	0.010
14	G37669	0.30	0.009
15	G37670	0.31	0.009
16	G37671	0.29	0.008
17	G37672	0.37	0.011
18	G37673	0.42	0.012
19	G37674	0.25	0.007
20	G37675	0.24	0.007
21	G37676	0.24	0.007
22	G37677	0.50	0.015
23	G37678	0.42	0.012
24	G37679	0.47	0.014
25	G37680	1.89	0.055
26	G37681	<0.03	<0.001
27	G37682	0.56	0.016
28	G37683	0.27	0.008

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5575 25-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G37684	0.38	0.011
30	G37685	0.37	0.011
31	G37686	0.88	0.026
32	G37687	0.82	0.024
33	G37688	0.40	0.012
34	G37689	0.41	0.012
35	G37690	0.27	0.008
QC DATA:			
Repeat:			
1	G37656	0.60	0.017
4	G37659	1.10	0.032
10	G37665	0.46	0.013
19	G37674	0.20	0.006
Resplits:			
1	G37656	0.59	0.017
Standard:			
SI25		1.79	0.052

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

1-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5575

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07097
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37656	1.2	0.35	15	20	<5	0.23	2	10	192	1649	4.96	<10	<0.01	46	53	0.01	3	950	76	<5	<20	15	<0.01	<10	2	<10	2	80
2	G37657	1.1	0.46	15	20	<5	0.31	2	10	94	1275	4.52	<10	0.07	89	70	<0.01	1	1170	60	<5	<20	14	<0.01	<10	3	<10	2	153
3	G37658	1.2	0.42	15	25	<5	0.26	1	8	155	1620	4.35	<10	0.13	140	83	<0.01	2	1120	34	<5	<20	14	<0.01	<10	4	<10	2	126
4	G37659	1.5	1.29	45	25	<5	0.24	<1	14	111	682	4.68	<10	0.93	539	56	<0.01	4	990	38	<5	<20	36	<0.01	<10	15	<10	2	325
5	G37660	1.1	0.21	30	25	<5	0.07	1	9	184	1422	3.82	<10	<0.01	30	117	<0.01	11	330	26	25	<20	11	<0.01	<10	2	<10	<1	63
6	G37661	1.4	0.19	170	25	<5	0.06	2	10	160	1545	4.31	<10	<0.01	31	150	<0.01	10	230	22	150	<20	8	<0.01	<10	<1	<10	<1	106
7	G37662	1.1	0.21	170	20	<5	0.08	1	7	192	876	3.31	<10	<0.01	28	70	0.01	10	330	20	100	<20	6	<0.01	<10	<1	<10	<1	81
8	G37663	0.9	0.21	120	25	<5	0.10	2	8	180	1281	3.16	<10	<0.01	35	102	0.01	10	360	50	70	<20	7	<0.01	<10	2	<10	<1	146
9	G37664	0.9	0.21	130	25	<5	0.10	2	8	188	1281	3.94	<10	<0.01	30	49	0.01	9	400	30	110	<20	6	<0.01	<10	2	<10	<1	167
10	G37665	0.8	0.21	90	25	<5	0.07	2	8	163	1325	4.73	<10	<0.01	25	72	0.01	8	280	42	75	<20	5	<0.01	<10	2	<10	<1	193
11	G37666	0.3	0.26	40	25	10	0.15	3	8	199	387	4.58	<10	<0.01	30	85	0.01	7	590	72	25	<20	5	<0.01	<10	3	<10	<1	385
12	G37667	0.9	0.15	85	25	<5	0.10	2	10	184	1659	4.17	<10	<0.01	27	95	0.01	7	420	64	45	<20	4	<0.01	<10	1	<10	<1	266
13	G37668	0.8	0.18	70	25	<5	0.09	2	8	185	1395	3.85	<10	<0.01	31	72	0.01	8	430	50	40	<20	5	<0.01	<10	3	<10	<1	337
14	G37669	0.7	0.18	70	25	<5	0.08	1	8	203	1281	3.58	<10	<0.01	37	61	0.01	8	370	36	40	<20	5	<0.01	<10	2	<10	<1	81
15	G37670	0.5	0.18	45	25	<5	0.08	2	11	178	1031	5.09	<10	0.02	31	129	0.01	7	380	118	10	<20	5	<0.01	<10	2	<10	<1	220
16	G37671	0.7	0.17	55	25	10	0.06	10	9	161	767	4.94	<10	<0.01	30	69	0.01	5	270	106	15	<20	5	<0.01	<10	2	<10	<1	1911
17	G37672	0.5	0.21	25	30	<5	0.15	1	8	190	1314	5.15	<10	<0.01	31	65	0.01	6	670	72	5	<20	7	<0.01	<10	1	<10	<1	108
18	G37673	0.8	0.16	55	25	<5	0.08	2	7	197	1213	3.81	<10	<0.01	31	75	0.01	6	340	100	5	<20	4	<0.01	<10	1	<10	<1	164
19	G37674	0.9	0.15	15	25	<5	0.03	<1	6	198	1152	3.53	<10	0.01	35	61	0.01	5	120	24	5	<20	3	<0.01	<10	1	<10	<1	28
20	G37675	1.2	0.16	140	25	<5	0.08	1	8	189	1476	4.01	<10	<0.01	32	38	0.01	5	340	24	45	<20	5	<0.01	<10	1	<10	<1	45
21	G37676	1.0	0.19	270	30	<5	0.06	1	5	177	1227	2.74	<10	0.03	36	42	0.01	5	270	30	30	<20	4	<0.01	<10	1	<10	<1	87
22	G37677	0.8	0.18	240	20	<5	0.08	1	11	157	1599	4.86	<10	0.01	29	163	0.01	9	380	52	15	<20	9	<0.01	<10	2	<10	<1	104
23	G37678	0.9	0.24	45	20	<5	0.09	2	12	148	1097	5.44	<10	0.03	49	54	0.01	11	410	32	5	<20	9	<0.01	<10	2	<10	1	243
24	G37679	0.6	0.29	10	25	<5	0.19	1	10	127	1059	4.09	<10	0.07	71	71	0.01	12	760	22	<5	<20	9	<0.01	<10	2	<10	1	179
25	G37680	4.0	1.14	35	50	<5	1.05	2	19	59	8656	4.19	20	0.63	211	584	0.04	62	310	56	25	<20	60	0.04	<10	35	<10	8	69

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37681	<0.2	1.04	10	245	<5	0.52	<1	7	90	10	2.20	<10	0.60	561	3	0.09	6	950	8	<5	<20	92	0.14	<10	38	<10	4	44
27	G37682	0.7	0.31	10	20	10	0.14	1	12	127	845	5.67	<10	0.07	81	53	0.01	14	590	22	<5	<20	21	<0.01	<10	3	<10	1	46
28	G37683	1.1	0.26	10	25	20	0.11	2	11	133	879	7.54	<10	0.08	79	98	0.01	10	490	60	<5	<20	9	<0.01	<10	2	<10	<1	107
29	G37684	1.7	0.36	10	20	<5	0.21	2	11	119	1410	5.25	<10	0.08	86	74	0.01	13	820	34	<5	<20	21	<0.01	<10	3	<10	1	119
30	G37685	1.5	0.32	10	20	<5	0.23	3	12	119	1886	5.64	<10	0.08	86	34	0.01	12	990	40	<5	<20	20	<0.01	<10	3	<10	1	251
31	G37686	1.9	0.32	20	25	15	0.42	4	13	147	954	7.21	<10	0.06	76	46	0.01	13	1970	114	<5	<20	17	<0.01	<10	3	<10	3	541
32	G37687	1.4	0.35	15	25	<5	0.30	1	12	131	1167	5.17	<10	0.10	96	32	0.01	14	1370	30	<5	<20	10	<0.01	<10	3	<10	2	86
33	G37688	1.5	0.45	15	20	<5	0.24	1	13	167	1830	5.08	<10	0.15	138	42	0.01	14	960	30	<5	<20	14	<0.01	<10	5	<10	1	99
34	G37689	1.4	0.37	20	20	<5	0.25	1	13	145	1891	5.01	<10	0.10	91	47	0.01	14	1400	26	<5	<20	13	<0.01	<10	4	<10	2	54
35	G37690	1.4	0.33	55	20	<5	0.30	2	11	138	1464	4.56	<10	0.11	105	150	0.01	13	1380	46	10	<20	12	<0.01	<10	3	<10	2	123
QC DATA:																													
Repeat:																													
1	G37656	1.3	0.35	15	20	<5	0.20	2	9	189	1659	4.96	<10	<0.01	45	61	0.01	3	950	68	<5	<20	15	<0.01	<10	2	<10	2	74
10	G37665	0.9	0.19	90	25	<5	0.07	2	8	162	1312	4.75	<10	<0.01	24	68	0.01	8	280	40	80	<20	5	<0.01	<10	2	<10	<1	193
19	G37674	0.7	0.15	15	25	<5	0.03	<1	7	199	1146	3.57	<10	0.01	49	58	0.01	5	120	22	5	<20	4	<0.01	<10	1	<10	<1	28
Resplit:																													
1	G37656	1.4	0.37	15	20	<5	0.23	15	11	189	1727	5.07	<10	<0.01	45	48	0.01	2	1000	72	<5	<20	15	<0.01	<10	3	<10	2	74
Standard:																													
Pb113		11.6	0.28	40	65	<5	1.67	38	2	<1	2255	1.10	<10	0.11	1497	68	0.02	1	90	5466	10	<20	80	0.01	<10	5	<10	1	6945

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa/jl
df/n5571
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5576

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

25-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07098
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35336	0.30	0.009
2	G35337	0.15	0.004
3	G35338	0.09	0.003
4	G35339	0.24	0.007
5	G35340	0.12	0.003
6	G35341	0.19	0.006
7	G35342	0.23	0.007
8	G35343	0.16	0.005
9	G35344	1.60	0.047
10	G35345	0.15	0.004
11	G35346	0.13	0.004
12	G35347	0.20	0.006
13	G35348	0.11	0.003
14	G35349	0.09	0.003
15	G35350	0.06	0.002
16	G35351	0.07	0.002
17	G35352	0.12	0.003
18	G35353	0.04	0.001
19	G35354	0.08	0.002
20	G35355	0.10	0.003
21	G35356	0.08	0.002
22	G35357	0.12	0.003
23	G35358	0.18	0.005
24	G35359	0.18	0.005
25	G35360	0.23	0.007
26	G35361	0.14	0.004
27	G35362	0.10	0.003

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5576 25-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G35363	0.10	0.003
29	G35364	0.10	0.003
30	G35365	<0.03	<0.001
31	G35366	0.06	0.002
32	G35367	0.11	0.003
33	G35368	0.07	0.002
34	G35369	0.06	0.002
35	G35370	0.04	0.001
QC DATA:			
Repeat:			
1	G35336	0.22	0.006
10	G35345	0.14	0.004
19	G35354	0.07	0.002
Resplits:			
1	G35336	0.21	0.006
Standard:			
SI25		1.82	0.053

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

1-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5576

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07098
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35336	1.2	0.78	10	95	<5	3.04	1	8	106	1841	8.21	<10	0.72	1561	<1	0.03	14	680	14	<5	<20	97	0.07	<10	241	<10	8	49
2	G35337	1.1	0.76	5	160	<5	1.46	<1	6	109	1492	3.12	<10	0.68	732	2	0.05	11	860	12	<5	<20	110	0.07	<10	77	<10	6	48
3	G35338	1.0	0.77	5	145	<5	0.98	<1	5	109	1379	3.26	<10	0.61	675	2	0.04	8	680	10	<5	<20	98	0.05	<10	95	<10	4	49
4	G35339	1.5	0.93	10	130	<5	1.41	<1	7	115	1334	3.51	<10	0.85	984	1	0.05	12	930	12	<5	<20	123	0.06	<10	79	<10	6	72
5	G35340	1.4	0.82	10	125	<5	2.05	1	6	102	1219	3.54	<10	0.70	1182	2	0.03	11	670	12	<5	<20	148	0.06	<10	67	<10	5	72
6	G35341	1.7	0.82	10	115	<5	1.65	<1	6	106	1444	3.95	<10	0.69	1012	2	0.03	10	730	12	<5	<20	111	0.05	<10	72	<10	5	65
7	G35342	2.5	0.74	10	40	<5	1.31	<1	8	91	2299	2.86	<10	0.51	803	3	0.03	8	810	14	<5	<20	101	0.03	<10	27	<10	5	51
8	G35343	2.0	0.89	10	35	<5	2.15	3	9	87	1720	3.45	<10	0.81	1238	1	0.03	12	850	22	<5	<20	174	0.05	<10	42	<10	5	163
9	G35344	0.2	0.77	1975	75	15	0.86	<1	26	22	51	4.65	10	2.02	628	<1	0.17	105	1110	12	5	<20	68	0.09	<10	19	<10	11	56
10	G35345	1.5	0.69	15	60	<5	1.67	<1	7	69	1672	2.47	<10	0.53	908	2	0.04	8	950	12	<5	<20	172	<0.01	<10	21	<10	5	47
11	G35346	1.7	0.90	15	45	<5	1.82	<1	7	85	1460	2.81	<10	0.74	1030	1	0.05	12	850	16	<5	<20	129	0.03	<10	35	<10	6	90
12	G35347	1.0	0.76	20	35	<5	1.48	<1	9	95	1550	2.67	<10	0.71	863	2	0.04	20	670	12	<5	<20	104	0.05	<10	30	<10	5	55
13	G35348	1.1	1.27	20	35	<5	1.71	2	9	73	1625	4.69	<10	1.26	1738	1	0.03	17	1190	28	<5	<20	131	0.06	<10	39	<10	6	154
14	G35349	1.1	0.84	25	35	<5	2.55	2	7	69	1188	3.59	<10	0.81	1857	2	0.01	11	1000	28	<5	<20	163	0.06	<10	32	<10	7	225
15	G35350	1.4	0.83	40	35	<5	2.17	8	6	65	1223	3.35	<10	0.75	1570	1	0.01	10	1110	68	<5	<20	189	0.05	<10	24	<10	7	750
16	G35351	1.7	0.84	15	35	<5	1.64	25	7	94	890	3.80	<10	0.74	1244	2	0.03	9	1000	120	<5	<20	125	0.06	<10	42	<10	4	1914
17	G35352	3.7	0.92	15	45	<5	3.16	<1	8	74	1266	3.22	<10	0.84	1862	<1	0.03	11	880	16	<5	<20	186	0.05	<10	49	<10	8	92
18	G35353	1.9	0.85	10	225	<5	1.28	1	5	81	879	2.91	<10	0.74	877	2	0.03	10	900	12	<5	<20	138	0.04	<10	64	<10	5	119
19	G35354	0.7	0.95	10	70	<5	1.58	1	7	140	857	3.01	<10	0.74	984	1	0.06	11	850	14	<5	<20	142	0.06	<10	65	<10	5	130
20	G35355	1.8	0.98	15	40	<5	0.83	3	6	97	1410	3.55	<10	0.86	1035	2	0.03	13	950	14	<5	<20	90	0.05	<10	54	<10	5	323
21	G35356	1.0	0.83	10	105	<5	0.79	<1	5	95	1130	2.99	<10	0.68	669	1	0.03	11	910	14	<5	<20	210	0.05	<10	60	<10	5	93
22	G35357	1.1	0.81	10	120	<5	0.85	<1	5	98	1239	2.96	<10	0.63	654	2	0.04	10	860	14	<5	<20	151	0.05	<10	59	<10	4	93
23	G35358	1.2	0.81	10	80	<5	1.69	<1	5	80	1344	3.30	<10	0.61	962	<1	0.03	11	1000	12	<5	<20	149	0.03	<10	52	<10	5	82
24	G35359	1.5	1.25	30	60	<5	1.46	2	13	83	1873	4.49	<10	1.11	1194	3	0.03	15	1130	26	<5	<20	111	0.06	<10	52	<10	5	256
25	G35360	1.7	1.02	10	100	<5	1.44	2	7	108	1667	2.68	<10	0.98	969	3	0.05	22	850	32	<5	<20	110	0.06	<10	61	<10	5	244

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35361	3.6	0.99	15	50	<5	1.89	77	8	83	2291	2.47	<10	1.05	1250	4	0.04	32	1000	156	<5	<20	130	0.06	<10	38	<10	7	7496
27	G35362	2.0	0.94	15	55	<5	2.01	3	8	106	1398	2.31	<10	0.86	1277	3	0.04	16	910	40	<5	<20	170	0.07	<10	41	<10	6	385
28	G35363	2.1	0.72	10	50	<5	1.12	<1	5	99	1512	2.61	<10	0.60	1135	4	0.05	10	460	44	<5	<20	88	0.01	<10	39	<10	4	83
29	G35364	2.7	0.79	20	35	<5	0.95	<1	8	94	2376	4.96	<10	0.63	1112	2	0.05	11	360	24	<5	<20	84	0.02	<10	47	<10	4	80
30	G35365	0.2	0.96	5	235	10	0.54	<1	6	83	7	2.20	<10	0.60	545	<1	0.08	6	960	8	<5	<20	69	0.14	<10	41	<10	5	43
31	G35366	1.1	0.69	10	55	<5	0.97	<1	4	128	981	2.44	<10	0.54	1005	3	0.06	11	550	10	<5	<20	90	0.01	<10	48	<10	4	62
32	G35367	1.4	0.81	20	35	<5	0.92	<1	8	98	1345	4.21	<10	0.73	1030	2	0.05	14	640	34	<5	<20	79	0.01	<10	64	<10	4	94
33	G35368	1.0	0.44	15	55	<5	1.58	<1	3	113	702	1.89	<10	0.36	1044	3	0.07	9	490	42	<5	<20	93	<0.01	<10	30	<10	5	51
34	G35369	1.6	0.50	30	30	10	1.23	22	5	100	831	2.96	<10	0.53	934	3	0.04	11	490	44	<5	<20	113	0.01	<10	44	<10	5	2164
35	G35370	1.1	0.53	5	50	<5	1.14	1	4	108	788	1.96	<10	0.46	886	7	0.07	9	400	76	<5	<20	103	0.02	<10	42	<10	3	118
QC DATA:																													
Repeat:																													
1	G35336	1.4	0.78	10	95	<5	3.11	1	8	101	1854	8.03	<10	0.71	1578	<1	0.03	14	680	12	<5	<20	98	0.06	<10	233	<10	8	48
10	G35345	1.6	0.64	15	50	<5	1.62	<1	6	65	1649	2.40	<10	0.52	875	2	0.03	8	940	10	<5	<20	167	<0.01	<10	20	<10	5	44
19	G35354	0.9	0.94	10	65	<5	1.59	1	6	135	864	2.97	<10	0.74	994	1	0.05	11	860	14	<5	<20	139	0.05	<10	62	<10	5	135
Resplit:																													
1	G35336	1.5	0.82	10	95	10	3.02	2	9	131	1882	8.63	<10	0.70	1538	<1	0.03	15	670	12	<5	<20	106	0.07	<10	252	<10	8	49
Standard:																													
Pb113		10.9	0.28	55	60	<5	1.89	38	2	<1	2209	1.09	<10	0.11	1487	63	0.02	<1	90	5440	5	<20	78	0.01	<10	7	<10	1	7053

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa/jl
dl/n5571
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5577

REVISED

Seabridge Gold Inc. 26-Sep-07
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07099
Submitted by: Peter Erwich.

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37691	0.27	0.008
2	G37692	0.21	0.006
3	G37693	0.45	0.013
4	G37694	0.49	0.014
5	G37695	0.33	0.010
6	G37696	0.28	0.008
7	G37697	0.33	0.010
8	G37698	0.39	0.011
9	G37699	0.39	0.011
10	G37700	0.69	0.020
11	G37701	0.41	0.012
12	G37702	0.48	0.014
13	G37703	0.39	0.011
14	G37704	0.56	0.016
15	G37705	0.48	0.014
16	G37706	0.22	0.006
17	G37707	0.24	0.007
18	G37708	0.29	0.008
19	G37709	0.44	0.013
20	G37710	0.98	0.029
21	G37711	<0.03	<0.001
22	G37712	0.99	0.029
23	G37713	0.29	0.008
24	G37714	0.24	0.007
25	G37715	0.24	0.007

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5577 26-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	G37716	0.31	0.009
27	G37717	0.46	0.013
28	G37718	0.25	0.007
29	G37719	0.36	0.010
30	G37720	0.39	0.011
31	G37721	0.45	0.013
32	G37722	0.36	0.010
33	G37723	0.40	0.012
34	G37724	0.39	0.011
35	G37725	0.39	0.011

QC DATA:

Repeat:

1	G37691	0.27	0.008
3	G37693	0.45	0.013
4	G37694	0.47	0.014
10	G37700	0.68	0.020
14	G37704	0.49	0.014
19	G37709	0.44	0.013

Resplits:

1	G37691	0.27	0.008

Standard:

Si25		1.83	0.053

AU: 30g FA/AA-Finish

Lynn Brazier

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
XLS/07

27-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5577
REVISED

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07099
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37691	1.5	0.33	80	30	<5	0.20	3	15	131	1248	3.99	<10	0.08	93	48	0.01	18	740	54	15	<20	14	<0.01	<10	6	<10	<1	144
2	G37692	0.7	0.33	20	35	<5	0.19	2	13	175	535	4.49	<10	0.07	88	60	0.01	16	780	84	<5	<20	13	0.02	<10	6	<10	<1	179
3	G37693	0.8	0.36	10	35	<5	0.22	1	14	180	1206	4.73	<10	0.11	98	47	0.01	17	930	54	<5	<20	14	0.01	<10	6	<10	<1	89
4	G37694	0.8	0.36	<5	35	<5	0.16	2	16	158	1473	4.71	<10	0.10	88	36	0.01	22	610	40	<5	<20	14	<0.01	<10	6	<10	<1	87
5	G37695	0.9	0.40	5	35	<5	0.18	<1	12	187	1071	4.08	<10	0.11	85	43	0.01	17	700	66	<5	<20	15	0.01	<10	6	<10	<1	84
6	G37696	0.9	0.35	<5	40	<5	0.15	1	13	145	1205	4.25	<10	0.07	81	32	0.01	16	610	32	<5	<20	18	0.01	<10	7	<10	<1	106
7	G37697	1.0	0.38	10	40	<5	0.30	<1	13	190	1259	3.77	<10	0.05	61	34	0.01	17	1320	28	<5	<20	16	<0.01	<10	7	<10	<1	25
8	G37698	0.7	0.30	<5	35	<5	0.14	<1	12	182	1125	4.03	<10	<0.01	36	41	0.01	16	580	22	<5	<20	11	<0.01	<10	5	<10	<1	16
9	G37699	1.1	0.34	<5	40	<5	0.21	1	14	163	1311	4.58	<10	0.02	48	42	0.01	21	900	24	<5	<20	13	<0.01	<10	7	<10	<1	32
10	G37700	1.5	0.40	10	40	<5	0.17	1	17	168	2089	4.32	<10	0.09	73	58	0.01	20	620	28	<5	<20	17	<0.01	<10	7	<10	<1	84
11	G37701	0.8	0.32	<5	30	<5	0.20	2	15	138	1394	4.36	<10	0.05	63	33	<0.01	20	830	28	<5	<20	22	<0.01	<10	6	<10	<1	37
12	G37702	0.8	0.37	10	30	<5	0.15	1	15	204	1671	4.22	<10	0.08	69	61	0.01	20	550	30	<5	<20	35	<0.01	<10	7	<10	<1	32
13	G37703	0.7	0.34	<5	35	<5	0.16	1	13	139	1495	3.97	<10	0.07	58	41	0.01	14	650	30	<5	<20	18	<0.01	<10	5	<10	<1	37
14	G37704	0.7	0.41	<5	30	<5	0.24	2	15	154	1182	4.35	<10	0.09	81	60	0.01	18	1030	30	<5	<20	16	<0.01	<10	6	<10	<1	109
15	G37705	1.0	0.38	15	30	<5	0.20	<1	17	142	1485	4.62	<10	0.09	88	39	0.01	18	800	20	<5	<20	20	0.01	<10	7	<10	<1	54
16	G37706	0.8	0.31	10	35	<5	0.11	1	12	208	1024	4.12	<10	0.05	59	56	0.01	18	440	28	<5	<20	24	<0.01	<10	5	<10	<1	23
17	G37707	1.5	0.30	45	35	<5	0.08	1	12	178	1284	3.61	<10	0.05	48	48	<0.01	17	240	34	10	<20	13	<0.01	<10	4	<10	<1	32
18	G37708	1.7	0.32	80	25	<5	0.08	<1	8	185	988	2.55	<10	0.09	65	60	0.01	10	280	32	10	<20	19	0.01	<10	4	<10	<1	67
19	G37709	3.4	0.63	250	45	<5	0.28	4	16	183	1749	4.89	<10	0.36	174	39	<0.01	22	1210	74	65	<20	17	0.02	<10	9	<10	<1	161
20	G37710	4.0	1.06	50	60	<5	0.68	4	16	58	3303	3.62	20	0.47	252	202	0.03	15	380	128	40	<20	34	0.05	<10	41	<10	6	146
21	G37711	<0.2	1.01	20	255	10	0.61	<1	7	90	10	2.15	<10	0.56	528	2	0.12	4	780	24	<5	<20	96	0.12	<10	47	<10	7	43
22	G37712	0.8	0.46	15	35	<5	0.36	4	15	125	996	5.10	<10	0.15	103	49	0.01	31	1640	28	35	<20	16	<0.01	<10	10	<10	<1	55
23	G37713	1.0	0.41	80	30	<5	0.12	1	10	190	717	3.78	<10	0.15	103	46	0.01	17	440	50	15	<20	8	0.01	<10	7	<10	<1	74
24	G37714	1.6	0.35	200	30	<5	0.11	3	11	154	1231	3.72	<10	0.08	67	53	0.01	14	390	68	35	<20	12	0.01	<10	5	<10	<1	107
25	G37715	1.5	0.39	160	30	<5	0.11	2	9	180	1557	2.82	<10	0.15	84	38	0.01	11	370	36	10	<20	17	<0.01	<10	4	<10	<1	80

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37716	2.1	0.47	275	30	<5	0.13	2	10	200	1352	3.32	<10	0.17	116	39	0.01	13	440	86	15	<20	16	0.01	<10	5	<10	<1	104
27	G37717	2.4	0.63	380	35	<5	0.13	4	13	188	1613	4.62	<10	0.37	193	112	0.01	14	410	524	25	<20	17	0.01	<10	8	<10	<1	179
28	G37718	2.6	0.50	200	25	<5	0.39	3	10	154	1024	3.45	<10	0.22	91	41	<0.01	14	1790	120	30	<20	12	<0.01	<10	7	<10	<1	119
29	G37719	1.9	0.39	80	30	<5	0.52	1	11	210	1129	3.88	<10	0.03	45	95	0.01	13	2380	26	<5	<20	24	<0.01	<10	5	<10	<1	54
30	G37720	2.1	0.28	50	35	<5	0.15	2	14	146	1199	4.94	<10	<0.01	26	122	0.01	16	590	20	5	<20	33	0.01	<10	4	<10	<1	41
31	G37721	0.9	0.26	30	25	<5	0.08	1	10	151	1291	3.54	<10	0.03	36	109	<0.01	11	250	18	<5	<20	10	<0.01	<10	4	<10	<1	77
32	G37722	0.7	0.31	15	30	<5	0.09	1	11	162	882	4.05	<10	0.06	51	90	0.01	13	320	22	<5	<20	19	0.01	<10	5	<10	<1	62
33	G37723	1.0	0.29	20	25	<5	0.11	3	11	153	1223	3.47	<10	0.04	39	66	0.01	22	350	18	35	<20	16	<0.01	<10	6	<10	<1	29
34	G37724	0.9	0.36	15	30	<5	0.36	1	14	133	1193	4.02	<10	0.02	64	76	0.01	18	1640	26	<5	<20	19	<0.01	<10	5	<10	1	71
35	G37725	1.1	0.41	20	40	<5	0.22	1	15	132	1249	4.60	<10	0.05	68	69	0.01	20	880	22	<5	<20	17	0.01	<10	7	<10	<1	29
QC DATA:																													
Repeat:																													
1	G37691	1.3	0.38	85	30	<5	0.21	3	16	136	1274	4.03	<10	0.08	97	45	0.01	18	780	58	15	<20	16	0.01	<10	7	<10	<1	145
10	G37700	1.4	0.41	5	40	<5	0.17	1	17	173	2049	4.28	<10	0.09	74	57	0.01	19	640	30	<5	<20	21	<0.01	<10	7	<10	<1	86
19	G37709	3.6	0.69	250	40	<5	0.28	4	16	188	1755	4.88	<10	0.38	178	38	0.01	21	1190	72	70	<20	14	<0.01	<10	10	<10	<1	164
Resplit:																													
1	G37691	1.4	0.32	80	30	<5	0.20	4	16	134	1234	4.17	<10	0.09	94	50	0.01	20	740	62	20	<20	15	0.01	<10	8	<10	<1	157
Standard:																													
Pb113		11.0	0.28	45	60	<5	1.67	38	2	6	2247	1.05	<10	0.10	1432	63	0.02	5	90	5472	30	<20	88	<0.01	<10	9	<10	<1	6995

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

JJ/nl
df/5577S
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5578

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

9-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07100
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37726	0.50	0.015
2	G37727	0.55	0.016
3	G37728	0.29	0.008
4	G37729	0.25	0.007
5	G37730	0.44	0.013
6	G37731	0.66	0.019
7	G37732	0.63	0.018
8	G37733	0.78	0.023
9	G37734	0.76	0.022
10	G37735	0.72	0.021
11	G37736	0.62	0.018
12	G37737	0.79	0.023
13	G37738	0.79	0.023
14	G37739	0.61	0.018
15	G37740	0.63	0.018
16	G37741	0.34	0.010
17	G37742	0.43	0.013
18	G37743	0.42	0.012
19	G37744	0.49	0.014
20	G37745	0.47	0.014
21	G37746	0.54	0.016
22	G37747	0.07	0.002
23	G37748	<0.03	<0.001
24	G37749	0.77	0.022
25	G37750	0.67	0.020
26	G37751	0.64	0.019
27	G37752	0.87	0.025
28	G37753	0.39	0.011

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5578 9-Oct-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G37754	0.83	0.024
30	G37755	0.44	0.013
31	G37756	0.57	0.017
32	G37757	0.41	0.012
33	G37758	0.54	0.016
34	G37759	0.54	0.016
35	G37760	0.53	0.015

QC DATA:

Repeat:

1	G37726	0.44	0.013
10	G37735	0.74	0.022
19	G37744	0.46	0.013

Resplits:

1	G37726	0.43	0.013

Standard:

OXI54		1.84	0.054

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

28-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5578

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07100
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37726	2.0	0.32	95	30	<5	0.19	3	17	141	1711	4.45	<10	0.04	48	75	0.01	23	620	32	15	<20	22	<0.01	<10	6	<10	<1	127
2	G37727	0.7	0.35	<5	30	<5	0.16	2	12	123	1553	4.74	<10	0.06	51	39	0.01	23	510	18	<5	<20	15	0.01	<10	8	<10	<1	51
3	G37728	0.8	0.34	10	30	<5	0.12	2	10	144	1255	3.44	<10	0.09	52	60	0.01	18	360	30	<5	<20	18	<0.01	<10	4	<10	<1	56
4	G37729	0.7	0.32	10	30	<5	0.09	<1	8	133	1546	2.80	<10	0.08	46	596	0.01	12	230	38	<5	<20	19	<0.01	<10	3	<10	<1	79
5	G37730	1.2	0.40	<5	30	<5	0.20	2	11	148	1618	3.76	<10	0.11	61	77	0.01	18	670	70	<5	<20	27	<0.01	<10	5	<10	<1	87
6	G37731	1.2	0.53	<5	40	<5	0.31	2	13	133	1361	4.57	<10	0.18	105	51	0.02	20	1100	56	<5	<20	27	0.01	<10	8	<10	<1	145
7	G37732	1.5	0.46	<5	35	<5	0.19	1	14	157	1739	4.35	<10	0.15	88	56	0.01	18	570	72	<5	<20	30	0.01	<10	7	<10	<1	74
8	G37733	1.6	0.56	<5	40	<5	0.22	3	14	114	1140	4.69	<10	0.22	141	50	0.02	21	770	46	<5	<20	18	0.01	<10	8	<10	<1	123
9	G37734	2.1	0.85	<5	40	<5	0.23	2	14	118	1476	4.72	<10	0.47	274	69	0.01	15	800	50	5	<20	18	0.01	<10	13	<10	<1	130
10	G37735	1.6	0.52	<5	40	<5	0.43	2	12	105	1115	4.32	<10	0.15	113	67	0.02	6	1700	80	<5	<20	24	0.01	<10	10	<10	1	75
11	G37736	1.8	0.67	<5	35	<5	0.34	5	14	148	1346	4.83	<10	0.28	163	63	0.02	11	1300	58	15	<20	33	<0.01	<10	13	<10	<1	137
12	G37737	1.4	0.65	<5	35	<5	0.39	1	14	111	1331	4.26	<10	0.20	146	67	0.02	5	1470	28	<5	<20	39	0.01	<10	12	<10	<1	76
13	G37738	1.1	1.39	<5	40	<5	0.35	2	17	103	1168	5.48	<10	0.73	419	130	0.02	7	1310	50	10	<20	28	0.02	<10	25	<10	<1	176
14	G37739	1.0	1.28	<5	40	<5	0.36	1	14	83	852	5.09	<10	0.66	387	80	0.02	7	1420	34	5	<20	20	0.02	<10	23	<10	<1	127
15	G37740	1.0	1.31	<5	40	<5	0.36	2	15	78	898	5.08	<10	0.66	393	75	0.02	7	1420	34	5	<20	21	0.02	<10	24	<10	<1	129
16	G37741	0.8	1.03	<5	35	<5	0.42	1	14	92	671	4.85	<10	0.47	281	60	0.02	5	1700	32	<5	<20	21	0.02	<10	19	<10	2	90
17	G37742	1.1	1.32	<5	40	<5	0.40	2	14	65	811	5.30	<10	0.67	384	81	0.02	6	1600	44	5	<20	21	0.02	<10	25	<10	2	127
18	G37743	0.9	1.87	<5	45	<5	0.37	2	13	81	742	5.39	<10	1.05	575	51	0.02	8	1410	42	25	<20	20	0.02	<10	38	<10	1	190
19	G37744	1.1	1.34	<5	35	<5	0.35	2	15	95	955	4.92	<10	0.76	385	53	0.02	7	1340	64	<5	<20	19	0.02	<10	28	<10	1	126
20	G37745	2.1	1.47	<5	40	<5	0.33	2	14	80	840	4.43	<10	0.85	414	69	0.02	6	1270	60	15	<20	18	0.02	<10	31	<10	2	157
21	G37746	1.3	0.88	<5	35	<5	0.34	<1	13	82	877	4.02	<10	0.34	225	71	0.02	<1	1350	32	<5	<20	18	0.02	<10	14	<10	2	67
22	G37747	0.2	0.91	70	150	15	0.26	8	66	269	429	>10	20	0.22	487	124	0.06	480	170	136	5	<20	9	0.05	<10	26	<10	<1	392
23	G37748	<0.2	0.99	<5	265	20	0.56	<1	6	137	5	1.93	<10	0.55	489	<1	0.14	6	710	20	<5	<20	90	0.10	<10	43	<10	5	43
24	G37749	1.0	1.25	<5	40	<5	0.31	2	14	120	1015	4.48	<10	0.59	354	128	0.02	7	1110	46	5	<20	16	0.01	<10	23	<10	<1	90
25	G37750	1.5	1.48	<5	35	<5	0.30	1	12	87	950	4.21	<10	0.80	452	213	0.02	6	1160	66	5	<20	13	0.02	<10	28	<10	1	124

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37751	2.0	0.98	<5	40	<5	0.37	1	15	110	1032	5.45	<10	0.40	286	73	0.02	7	1380	58	<5	<20	27	0.02	<10	18	<10	<1	57
27	G37752	2.7	1.36	<5	45	<5	0.34	2	18	90	1245	5.84	<10	0.70	459	80	0.02	7	1300	58	10	<20	28	0.02	<10	25	<10	<1	82
28	G37753	1.4	1.90	5	40	<5	0.34	<1	13	56	667	4.89	<10	1.14	693	65	0.02	4	1370	44	5	<20	31	0.02	<10	39	<10	3	117
29	G37754	1.7	2.00	<5	45	<5	0.31	2	15	69	983	5.50	<10	1.23	758	63	0.02	7	1160	54	15	<20	27	0.02	<10	41	<10	1	134
30	G37755	1.3	1.90	<5	40	<5	0.30	2	14	65	792	4.32	<10	1.25	700	52	0.02	6	1190	66	15	<20	23	0.02	<10	42	<10	2	140
31	G37756	1.7	1.65	<5	35	<5	0.32	2	15	104	905	4.91	<10	1.03	549	194	0.02	8	1260	80	15	<20	23	0.02	<10	40	<10	2	102
32	G37757	1.1	1.55	10	35	<5	0.33	1	12	93	729	4.06	<10	0.98	500	148	0.02	6	1290	56	10	<20	34	0.02	<10	35	<10	2	103
33	G37758	1.3	1.92	5	40	<5	0.32	8	15	77	859	5.08	<10	1.30	668	150	0.02	28	1240	60	130	<20	32	<0.01	<10	46	<10	2	156
34	G37759	1.4	1.37	5	35	<5	0.37	2	14	85	1117	4.78	<10	0.81	439	65	0.02	6	1410	80	5	<20	35	0.02	<10	30	<10	2	98
35	G37760	1.4	1.49	<5	35	<5	0.37	3	13	96	817	4.75	<10	0.88	462	45	0.02	8	1460	90	20	<20	33	0.02	<10	32	<10	2	103
QC DATA:																													
Repeat:																													
1	G37726	1.8	0.34	95	35	<5	0.19	3	17	141	1681	4.30	<10	0.04	48	79	0.01	22	610	32	15	<20	20	<0.01	<10	6	<10	<1	122
10	G37735	1.5	0.55	<5	35	<5	0.43	2	12	109	1109	4.33	<10	0.15	114	76	0.02	5	1710	76	<5	<20	19	0.01	<10	10	<10	1	76
19	G37744	1.0	1.36	<5	45	<5	0.34	1	15	97	949	4.86	<10	0.75	382	54	0.02	7	1330	66	5	<20	17	0.02	<10	29	<10	1	125
Resplit:																													
1	G37726	1.9	0.34	80	30	<5	0.18	3	15	135	1662	4.37	<10	0.05	47	78	0.01	22	570	32	20	<20	18	0.01	<10	6	<10	<1	131
Standard:																													
Pb113		11.9	0.28	40	65	<5	1.69	40	2	6	2289	1.04	<10	0.11	1439	81	0.02	4	90	5502	10	<20	84	<0.01	<10	8	<10	<1	6915

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5578
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5579

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

25-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 070101
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35371	0.17	0.005
2	G35372	0.12	0.003
3	G35373	0.14	0.004
4	G35374	0.15	0.004
5	G35375	0.10	0.003
6	G35376	<0.03	<0.001
7	G35377	0.18	0.005
8	G35378	0.14	0.004
9	G35379	0.13	0.004
10	G35380	0.15	0.004
11	G35381	0.23	0.007
12	G35382	0.15	0.004
13	G35383	0.27	0.008
14	G35384	0.15	0.004
15	G35385	0.09	0.003
16	G35386	0.12	0.003
17	G35387	0.08	0.002
18	G35388	0.10	0.003
19	G35389	0.16	0.005
20	G35390	1.68	0.049
21	G35391	0.16	0.005
22	G35392	0.20	0.006
23	G35393	0.11	0.003
24	G35394	0.16	0.005
25	G35395	0.23	0.007
26	G35396	0.18	0.005
27	G35397	0.13	0.004
28	G35398	0.09	0.003

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5579 25-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G35399	0.11	0.003
30	G35400	0.10	0.003
31	G35401	0.14	0.004
32	G35402	0.93	0.027
33	G35403	0.67	0.020
34	G35404	0.36	0.010
35	G35405	0.09	0.003
QC DATA:			
Repeat:			
1	G35371	0.20	0.006
10	G35380	0.14	0.004
19	G35389	0.14	0.004
Resplits:			
1	G35371	0.15	0.004
Standard:			
SI25		1.80	0.052

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

1-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5579

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 070101
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35371	0.8	0.70	<5	80	<5	4.57	<1	7	102	964	1.96	<10	0.63	2086	16	0.06	11	400	38	<5	<20	331	0.05	<10	60	<10	7	123
2	G35372	0.7	1.11	15	110	<5	3.27	2	15	85	1047	3.82	10	1.08	1611	25	0.08	26	870	60	20	<20	386	0.09	<10	111	<10	6	180
3	G35373	0.4	0.70	10	105	<5	2.72	<1	8	112	824	2.58	10	0.63	1263	8	0.06	15	400	48	10	<20	176	0.08	<10	103	<10	5	73
4	G35374	0.6	0.83	20	95	<5	3.44	<1	12	89	1245	2.29	10	0.79	1341	23	0.05	18	980	52	5	<20	264	0.10	<10	74	<10	9	75
5	G35375	0.4	0.97	5	140	<5	1.81	2	15	85	897	3.78	10	0.85	895	14	0.05	23	900	44	15	<20	140	0.12	<10	86	<10	7	87
6	G35376	<0.2	1.05	10	275	15	0.62	<1	6	135	6	2.10	<10	0.61	540	4	0.12	7	790	24	10	<20	100	0.12	<10	47	<10	6	49
7	G35377	0.4	0.68	<5	170	<5	2.11	1	9	109	513	3.31	<10	0.52	928	9	0.09	13	380	26	<5	<20	210	0.08	<10	124	<10	3	72
8	G35378	0.4	0.93	10	120	<5	1.41	<1	10	87	975	2.17	<10	0.89	705	6	0.07	14	930	26	<5	<20	121	0.09	<10	65	<10	6	75
9	G35379	0.4	1.38	15	165	<5	2.58	1	11	81	899	3.96	<10	1.46	1207	10	0.07	23	970	32	25	<20	222	0.08	<10	121	<10	5	111
10	G35380	0.5	1.02	20	65	<5	1.03	<1	9	66	756	1.38	<10	1.03	555	9	0.07	28	600	30	10	<20	79	0.08	<10	63	<10	10	68
11	G35381	0.6	1.05	20	140	<5	1.03	5	10	118	1297	2.32	<10	1.18	614	18	0.09	46	540	24	85	<20	111	<0.01	<10	91	<10	6	68
12	G35382	0.6	1.11	10	280	<5	0.90	<1	7	153	762	2.47	<10	1.18	632	6	0.10	47	600	26	10	<20	99	0.07	<10	114	<10	5	76
13	G35383	0.7	0.93	5	185	<5	0.83	<1	8	105	1206	2.08	<10	0.88	487	6	0.06	25	660	24	<5	<20	114	0.06	<10	78	<10	7	49
14	G35384	1.0	1.33	15	110	<5	2.43	<1	17	69	1674	2.89	<10	1.33	1026	12	0.05	29	1130	34	15	<20	275	0.07	<10	76	<10	9	83
15	G35385	0.5	0.96	15	125	<5	1.51	<1	10	83	919	3.04	<10	0.80	734	7	0.05	21	620	26	10	<20	169	0.05	<10	60	<10	5	72
16	G35386	0.6	0.88	20	115	<5	1.36	<1	6	76	754	2.59	<10	0.71	679	5	0.05	13	790	24	10	<20	170	0.02	<10	65	<10	4	63
17	G35387	0.5	0.86	10	50	<5	1.42	<1	8	86	618	2.94	<10	0.69	731	5	0.03	11	700	24	10	<20	154	0.03	<10	50	<10	4	94
18	G35388	0.9	0.84	20	45	<5	1.36	<1	9	96	1055	3.13	<10	0.68	727	7	0.05	18	740	30	10	<20	125	0.04	<10	55	<10	4	79
19	G35389	1.6	1.16	5	50	<5	1.65	1	19	101	2013	4.22	<10	1.08	943	12	0.06	19	560	34	10	<20	161	0.09	<10	81	<10	4	141
20	G35390	0.3	0.61	2250	75	10	0.70	1	28	27	59	4.67	10	1.92	740	5	0.13	107	1110	20	15	<20	64	0.09	<10	22	<10	8	52
21	G35391	0.8	1.47	30	55	<5	3.14	1	20	63	1208	3.59	<10	1.45	1316	8	0.05	25	920	36	15	<20	268	0.09	<10	60	<10	9	145
22	G35392	0.8	1.19	10	40	<5	2.35	2	13	84	1244	3.37	<10	1.15	1037	9	0.05	22	680	30	25	<20	232	0.05	<10	83	<10	6	135
23	G35393	0.7	0.86	30	45	<5	1.84	<1	11	82	1082	1.92	<10	0.82	733	9	0.07	18	980	28	5	<20	243	0.06	<10	64	<10	6	106
24	G35394	1.1	1.10	25	45	<5	1.03	<1	20	101	1895	3.29	<10	1.22	702	33	0.08	25	710	32	10	<20	88	0.08	<10	96	<10	5	128
25	G35395	1.0	1.17	15	60	<5	1.55	<1	13	103	1177	3.45	<10	1.28	794	17	0.05	22	960	42	10	<20	123	0.09	<10	119	<10	6	103

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35396	0.6	1.28	<5	90	<5	1.85	1	11	87	850	4.21	<10	1.26	924	15	0.04	20	1130	30	10	<20	145	0.07	<10	157	<10	4	97
27	G35397	0.7	1.39	15	70	<5	1.77	<1	11	135	784	4.24	<10	1.28	900	13	0.08	23	1200	32	15	<20	146	0.09	<10	157	<10	5	95
28	G35398	0.4	1.50	10	85	<5	1.99	<1	13	101	474	4.28	<10	1.39	943	14	0.07	24	1430	36	10	<20	158	0.06	<10	133	<10	5	104
29	G35399	0.9	1.80	20	50	<5	3.46	1	16	76	835	4.40	<10	1.90	1420	16	0.05	24	1300	42	15	<20	360	0.10	<10	129	<10	7	150
30	G35400	1.9	1.94	35	55	<5	4.07	<1	18	106	1374	4.05	<10	2.14	1487	15	0.05	47	1080	42	10	<20	452	0.12	<10	116	<10	6	124
31	G35401	2.4	1.89	10	50	<5	4.95	3	17	89	1278	4.78	<10	2.12	2295	26	0.04	31	950	68	10	<20	290	0.12	<10	110	<10	7	318
32	G35402	2.6	2.08	<5	55	<5	2.63	4	20	69	1210	8.08	<10	2.35	2351	25	0.05	28	820	106	25	<20	261	0.12	<10	144	<10	3	202
33	G35403	0.6	1.95	40	50	<5	3.21	3	16	73	326	6.74	<10	2.05	1935	21	0.03	30	780	46	50	<20	939	0.09	<10	174	<10	4	99
34	G35404	1.5	0.89	80	45	<5	1.70	<1	11	121	1377	3.30	<10	0.90	937	19	0.05	17	810	36	15	<20	117	0.04	<10	73	<10	5	79
35	G35405	1.4	1.24	25	45	<5	2.55	2	11	104	1257	3.45	<10	1.35	1515	17	0.04	19	730	34	25	<20	165	0.03	<10	96	<10	5	121
QC DATA:																													
Repeat:																													
1	G35371	1.0	0.71	5	70	<5	4.61	1	7	104	974	1.99	<10	0.64	2106	17	0.06	13	410	38	<5	<20	337	0.04	<10	61	<10	7	124
10	G35380	0.5	1.02	20	70	<5	1.03	<1	9	67	750	1.39	<10	1.02	553	8	0.07	27	600	32	5	<20	80	0.08	<10	63	<10	10	69
19	G35389	1.6	1.14	20	45	<5	1.63	1	18	101	1970	4.17	<10	1.07	927	11	0.06	20	540	34	5	<20	156	0.09	<10	81	<10	4	139
Resplit:																													
1	G35371	0.9	0.74	5	75	<5	4.64	1	7	110	911	2.03	<10	0.68	2025	14	0.06	11	440	42	5	<20	364	0.04	<10	66	<10	9	127
Standard:																													
Pb113		10.8	0.29	40	55	<5	1.69	46	2	7	2395	1.05	<10	0.11	1475	64	0.02	4	90	5532	30	<20	83	<0.01	<10	9	<10	<1	7046

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5578
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5580

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

25-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07102
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35406	0.08	0.002
2	G35407	0.13	0.004
3	G35408	0.11	0.003
4	G35409	0.05	0.001
5	G35410	0.10	0.003
6	G35411	0.16	0.005
7	G35412	0.15	0.004
8	G35413	0.16	0.005
9	G35414	0.09	0.003
10	G35415	0.11	0.003
11	G35416	<0.03	<0.001
12	G35417	0.07	0.002
13	G35418	0.23	0.007
14	G35419	0.17	0.005
15	G35420	0.21	0.006
16	G35421	0.17	0.005
17	G35422	0.09	0.003
18	G35423	0.15	0.004
19	G35424	0.12	0.003
20	G35425	0.18	0.005
21	G35426	0.14	0.004
22	G35427	0.09	0.003
23	G35428	0.30	0.009
24	G35429	0.49	0.014
25	G35430	0.12	0.003
26	G35431	0.18	0.005
27	G35432	0.11	0.003
28	G35433	0.08	0.002

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5580 25-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G35434	0.30	0.009
30	G35435	0.12	0.003
31	G35436	0.21	0.006
32	G35437	0.10	0.003
33	G35438	0.08	0.002
34	G35439	0.08	0.002
35	G35440	0.11	0.003

QC DATA:

Repeat:

1	G35406	0.05	0.001
10	G35415	0.11	0.003
19	G35424	0.12	0.003

Resplits:

1	G35406	0.07	0.002

Standard:

SI25		1.82	0.053

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5580

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1


No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07102
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35406	1.0	1.14	15	45	<5	1.08	2	12	80	436	488.32	<10	1.20	1090	9	0.05	18	1110	30	15	<20	76	0.07	<10	83	<10	5	184
2	G35407	1.1	1.03	15	50	<5	1.31	2	13	80	715	800.80	<10	1.07	1157	11	0.06	20	1120	20	5	<20	111	0.06	<10	76	<10	6	173
3	G35408	0.8	1.16	20	45	<5	1.65	<1	13	80	525	588.00	<10	1.21	1339	10	0.06	19	1130	20	10	<20	139	0.09	<10	87	<10	6	134
4	G35409	0.7	1.02	20	65	<5	1.37	2	12	100	549	614.88	<10	1.05	1099	12	0.10	16	780	24	<5	<20	95	0.08	<10	83	<10	3	194
5	G35410	1.1	1.33	25	45	<5	0.61	2	22	85	1017	1139.04	<10	1.47	1127	25	0.05	35	1050	24	5	<20	41	0.08	<10	93	<10	4	220
6	G35411	1.2	1.78	10	100	<5	4.78	1	16	65	1181	1322.72	<10	2.14	2687	17	0.03	32	820	20	15	<20	449	0.12	<10	90	<10	7	106
7	G35412	1.2	0.93	<5	130	<5	3.43	1	14	61	941	1053.92	<10	0.73	1779	8	0.05	17	1330	16	<5	<20	420	0.10	<10	85	<10	2	64
8	G35413	1.7	0.92	<5	50	<5	1.50	2	19	85	1305	1461.60	<10	0.74	1213	13	0.06	24	950	24	10	<20	110	0.06	<10	88	<10	3	104
9	G35414	1.2	0.82	10	60	<5	0.60	<1	12	100	869	973.28	<10	0.68	839	8	0.06	18	670	14	<5	<20	46	0.04	<10	82	<10	2	76
10	G35415	1.5	0.92	15	65	<5	1.03	<1	15	91	904	1012.48	<10	0.81	937	8	0.08	21	970	18	5	<20	73	0.10	<10	84	<10	3	67
11	G35416	<0.2	1.15	10	240	10	0.66	<1	7	196	6	6.72	<10	0.54	537	4	0.16	9	900	16	10	<20	108	0.11	<10	45	<10	6	35
12	G35417	1.2	1.10	10	60	<5	2.17	<1	14	80	696	779.52	<10	0.99	1620	7	0.05	21	1090	18	<5	<20	212	0.09	<10	96	<10	5	72
13	G35418	2.5	1.16	<5	50	<5	1.12	2	18	75	1156	1294.72	<10	1.04	1337	10	0.04	25	1130	20	15	<20	72	0.10	<10	73	<10	3	67
14	G35419	3.1	0.71	30	50	<5	0.68	<1	10	104	503	563.36	<10	0.68	745	14	0.04	15	870	48	10	<20	59	0.07	<10	63	<10	3	44
15	G35420	2.4	0.61	30	60	<5	1.36	<1	12	101	381	426.72	<10	0.56	741	15	0.06	13	840	44	<5	<20	113	0.08	<10	62	<10	6	47
16	G35421	2.0	0.92	15	55	<5	2.53	<1	13	96	772	864.64	<10	0.88	1336	18	0.05	21	990	26	5	<20	155	0.11	<10	79	<10	8	62
17	G35422	0.8	1.16	20	60	<5	2.06	<1	16	82	549	614.88	<10	1.09	1169	14	0.10	23	1300	22	15	<20	174	0.12	<10	89	<10	5	56
18	G35423	0.8	1.38	25	90	<5	2.39	<1	18	76	858	960.96	<10	1.51	1347	11	0.06	32	1070	22	20	<20	177	0.11	<10	78	<10	5	77
19	G35424	1.1	1.49	25	155	<5	3.05	<1	15	52	1605	1797.60	<10	1.86	1356	12	0.05	20	1220	38	15	<20	339	0.13	<10	76	<10	6	76
20	G35425	0.5	1.25	20	230	<5	2.69	<1	13	64	1000	1120.00	<10	1.20	1101	20	0.05	24	1870	30	15	<20	268	0.12	<10	104	<10	10	58
21	G35426	0.4	1.12	15	120	<5	2.06	<1	11	89	832	931.84	<10	1.22	929	8	0.07	21	1100	24	15	<20	148	0.12	<10	83	<10	6	49
22	G35427	0.4	1.12	20	155	<5	1.90	<1	10	77	676	757.12	<10	1.25	946	9	0.06	24	1490	20	20	<20	153	0.10	<10	93	<10	6	52
23	G35428	0.7	0.97	15	110	<5	3.02	<1	14	74	724	810.88	<10	0.97	1268	13	0.07	17	920	22	5	<20	193	0.10	<10	79	<10	5	55
24	G35429	0.8	1.55	20	100	<5	4.13	<1	17	60	972	1088.64	<10	1.61	2019	22	0.05	21	990	30	15	<20	246	0.12	<10	101	<10	5	91
25	G35430	1.0	1.59	35	70	<5	3.70	<1	17	83	645	722.40	<10	1.88	1738	8	0.06	14	1630	78	10	<20	227	0.14	<10	151	<10	6	128

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35431	2.9	1.67	<5	45	<5	3.57	13	18	82	1105	1237.60	<10	1.93	1700	15	0.04	14	1850	962	20	<20	167	0.12	<10	154	<10	<1	653
27	G35432	0.7	1.47	50	105	<5	4.32	<1	18	64	831	930.72	<10	1.70	1447	9	0.03	19	1040	40	20	<20	210	0.14	<10	81	<10	6	80
28	G35433	0.6	1.71	25	30	<5	4.55	<1	16	79	694	777.28	<10	1.82	1619	10	0.04	15	1930	43	20	<20	258	0.13	<10	161	<10	2	89
29	G35434	3.1	1.18	40	60	<5	1.05	2	22	54	2638	3.58	20	0.56	201	207	0.03	11	610	60	10	<20	47	0.06	<10	46	<10	5	270
30	G35435	1.4	1.63	20	80	<5	3.54	<1	17	87	673	753.76	<10	1.87	1405	9	0.05	15	2100	58	15	<20	137	0.13	<10	170	<10	5	115
31	G35436	2.8	1.28	20	55	<5	6.04	2	17	78	806	902.72	<10	1.23	1777	11	0.04	17	1950	60	20	<20	264	0.11	<10	133	<10	3	89
32	G35437	1.5	0.69	20	70	<5	2.19	<1	9	92	519	581.28	<10	0.64	805	7	0.06	14	970	34	10	<20	86	0.08	<10	65	<10	4	57
33	G35438	1.5	0.89	30	80	<5	1.44	<1	12	97	711	796.32	<10	0.91	808	10	0.06	20	1090	30	15	<20	66	0.10	<10	88	<10	4	83
34	G35439	1.6	1.14	30	60	<5	2.63	<1	17	84	904	1012.48	<10	1.34	1792	11	0.05	25	1430	60	15	<20	102	0.13	<10	86	<10	5	170
35	G35440	2.6	0.81	40	40	<5	1.06	21	13	96	654	732.48	<10	0.88	1097	25	0.04	22	1170	456	20	<20	38	0.10	<10	57	<10	2	1473
QC DATA:																													
Repeat:																													
1	G35406	1.0	1.09	20	50	<5	1.44	2	12	77	427	478.24	<10	1.16	1087	8	0.05	18	1150	34	15	<20	74	0.08	<10	79	<10	5	189
10	G35415	1.4	0.90	10	65	<5	1.42	<1	16	92	889	995.68	<10	0.79	970	7	0.07	21	1050	22	5	<20	75	0.09	<10	82	<10	3	74
19	G35424	1.1	1.48	20	170	<5	4.27	<1	16	55	1647	1844.64	<10	1.82	1385	13	0.05	22	1300	46	20	<20	339	0.12	<10	74	<10	5	82
Resplit:																													
1	G35406	0.8	1.09	15	45	<5	1.44	3	14	81	402	2.63	<10	1.16	1121	9	0.05	20	1140	40	15	<20	69	0.08	<10	83	<10	5	259
Standard:																													
Pb113		11.6	0.25	40	65	<5	1.65	39	2	5	2238	1.10	<10	0.09	1518	69	0.02	3	100	5538	15	<20	86	0.01	<10	4	<10	<1	7003

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish



ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5580
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5581

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

25-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07103
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37761	0.42	0.012
2	G37762	0.46	0.013
3	G37763	0.55	0.016
4	G37764	0.44	0.013
5	G37765	0.40	0.012
6	G37766	0.46	0.013
7	G37767	0.34	0.010
8	G37768	0.51	0.015
9	G37769	0.48	0.014
10	G37770	<0.03	<0.001
11	G37771	0.49	0.014
12	G37772	0.31	0.009
13	G37773	0.36	0.010
14	G37774	0.30	0.009
15	G37775	0.43	0.013
16	G37776	0.39	0.011
17	G37777	0.48	0.014
18	G37778	0.31	0.009
19	G37779	0.31	0.009
20	G37780	0.52	0.015
21	G37781	0.31	0.009
22	G37782	0.33	0.010
23	G37783	0.33	0.010
24	G37784	0.79	0.023
25	G37785	0.99	0.029
26	G37786	1.16	0.034
27	G37787	1.26	0.037

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5581 25-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G37788	0.82	0.024
29	G37789	0.61	0.018
30	G37790	1.87	0.055
31	G37791	0.48	0.014
32	G37792	0.80	0.023
33	G37793	0.62	0.018
34	G37794	0.55	0.016
35	G37795	0.55	0.016
QC DATA:			
Repeat:			
1	G37761	0.39	0.011
19	G37779	0.34	0.010
Resplits:			
1	G37761	0.41	0.012
Standard:			
SI25		1.79	0.052

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

1-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5581

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07103
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37761	1.6	1.75	15	35	<5	0.35	2	17	109	976	5.36	<10	1.03	603	505	0.02	4	1290	100	10	<20	35	0.03	<10	42	<10	<1	104
2	G37762	1.6	1.51	<5	35	<5	0.35	2	20	114	871	5.63	<10	0.85	541	101	0.02	5	1290	106	<5	<20	29	0.03	<10	33	<10	<1	83
3	G37763	1.1	2.54	20	35	<5	0.36	2	15	84	766	5.40	<10	1.63	1015	84	0.02	6	1350	66	20	<20	25	0.03	<10	56	<10	1	123
4	G37764	1.4	1.44	10	30	<5	0.37	2	15	92	805	5.29	<10	0.82	509	179	0.02	5	1370	56	<5	<20	29	0.03	<10	31	<10	<1	76
5	G37765	0.9	2.36	10	35	<5	0.40	1	12	70	575	4.53	<10	1.58	859	67	0.02	5	1540	56	15	<20	40	0.03	<10	56	<10	3	147
6	G37766	1.4	2.51	25	35	<5	0.35	1	16	92	929	5.82	<10	1.68	911	64	0.02	6	1330	66	15	<20	33	0.03	<10	58	<10	1	149
7	G37767	1.3	1.99	30	30	<5	0.38	1	17	94	720	4.80	<10	1.24	618	74	0.02	5	1460	88	10	<20	23	0.02	<10	45	<10	2	141
8	G37768	1.4	1.55	20	25	<5	0.42	2	15	87	864	4.13	<10	0.93	465	127	0.02	5	1620	80	10	<20	22	0.02	<10	38	<10	2	109
9	G37769	1.0	1.65	<5	35	<5	0.39	1	14	92	764	4.50	<10	0.99	492	109	0.02	5	1510	74	<5	<20	34	0.02	<10	39	<10	1	93
10	G37770	<0.2	1.04	15	295	5	0.62	<1	6	91	5	2.22	<10	0.57	538	3	0.13	5	780	20	<5	<20	90	0.12	<10	45	<10	2	43
11	G37771	1.6	1.60	10	40	<5	0.35	3	19	87	1060	6.13	<10	0.91	467	132	0.02	9	1320	106	15	<20	38	0.02	<10	36	<10	<1	105
12	G37772	0.9	2.20	15	35	<5	0.36	1	13	59	568	4.70	<10	1.44	680	72	0.02	5	1430	58	15	<20	37	0.02	<10	52	<10	2	152
13	G37773	1.0	1.55	10	30	<5	0.38	2	13	91	641	4.92	<10	0.91	439	115	0.02	5	1460	70	5	<20	37	0.02	<10	37	<10	2	125
14	G37774	1.2	1.99	20	35	<5	0.40	2	16	96	662	5.23	<10	1.22	570	84	0.03	6	1590	60	20	<20	44	0.02	<10	47	<10	3	176
15	G37775	1.2	1.82	15	35	<5	0.39	1	17	93	904	5.02	<10	1.11	502	113	0.04	5	1530	80	<5	<20	44	0.03	<10	49	<10	3	182
16	G37776	1.1	2.15	30	35	<5	0.42	3	17	83	809	5.41	<10	1.27	563	72	0.04	5	1640	242	10	<20	43	0.03	<10	50	<10	2	296
17	G37777	0.9	1.29	10	30	<5	0.37	<1	14	78	801	4.72	<10	0.70	364	130	0.03	6	1460	38	10	<20	26	0.02	<10	28	<10	1	149
18	G37778	1.0	1.31	15	35	<5	0.38	<1	15	105	690	4.52	<10	0.70	351	172	0.03	5	1520	48	<5	<20	31	0.02	<10	30	<10	2	187
19	G37779	0.7	2.08	15	45	<5	0.37	<1	17	89	313	5.47	<10	1.25	550	101	0.03	5	1460	48	10	<20	43	0.03	<10	48	<10	2	189
20	G37780	0.8	1.27	15	40	<5	0.37	<1	21	86	313	6.37	<10	0.65	306	71	0.03	5	1490	36	<5	<20	27	0.03	<10	27	<10	<1	95
21	G37781	0.4	2.03	10	40	<5	0.37	<1	15	95	117	4.67	<10	1.25	564	83	0.03	4	1510	38	15	<20	29	0.02	<10	47	<10	1	163
22	G37782	0.5	2.31	20	35	<5	0.39	1	18	76	356	5.43	<10	1.54	712	83	0.02	9	1560	44	30	<20	28	0.02	<10	56	<10	1	179
23	G37783	1.8	1.20	10	30	<5	0.18	2	14	164	919	5.24	<10	0.73	388	47	0.02	15	540	60	10	<20	14	0.02	<10	21	<10	<1	98
24	G37784	2.4	1.16	<5	40	<5	0.22	1	15	90	2304	7.11	<10	0.50	297	18	0.02	17	710	50	<5	<20	17	0.03	<10	17	<10	<1	90
25	G37785	2.7	1.34	10	45	<5	0.23	2	23	108	2689	9.08	<10	0.49	288	627	0.02	23	690	34	<5	<20	19	0.03	<10	21	<10	<1	106

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37786	3.0	1.24	<5	45	<5	0.19	2	20	94	2680	8.61	<10	0.39	204	607	0.03	20	500	30	<5	<20	18	0.03	<10	20	<10	<1	98
27	G37787	2.8	1.59	<5	45	<5	0.28	2	18	99	2513	8.14	<10	0.62	264	40	0.03	16	910	30	5	<20	21	0.03	<10	27	<10	<1	132
28	G37788	2.7	1.02	<5	40	<5	0.33	2	20	93	1889	7.23	<10	0.41	179	23	0.03	9	1220	34	<5	<20	16	0.03	<10	17	<10	<1	83
29	G37789	1.7	0.92	<5	30	<5	0.33	1	17	89	1111	6.19	<10	0.41	166	130	0.02	7	1240	34	<5	<20	18	0.03	<10	15	<10	<1	73
30	G37790	4.0	1.08	30	35	<5	0.99	2	21	61	8721	4.19	<10	0.56	194	601	0.04	61	<10	66	20	<20	56	0.03	<10	42	<10	5	70
31	G37791	1.4	0.99	<5	30	<5	0.35	1	18	83	1024	6.07	<10	0.42	164	117	0.03	7	1410	34	<5	<20	17	0.03	<10	13	<10	<1	68
32	G37792	1.1	1.43	10	30	<5	0.38	2	16	61	1037	6.09	<10	0.67	250	49	0.03	7	1450	30	<5	<20	23	0.02	<10	27	<10	<1	101
33	G37793	1.1	1.59	5	35	<5	0.37	2	16	74	1124	6.45	<10	0.77	287	38	0.03	9	1380	32	15	<20	26	0.02	<10	28	<10	<1	107
34	G37794	1.8	1.36	5	35	<5	0.33	1	18	98	1369	7.46	<10	0.61	261	60	0.03	11	1180	32	<5	<20	24	0.03	<10	23	<10	<1	87
35	G37795	1.7	1.06	<5	40	<5	0.36	2	18	82	1341	6.17	<10	0.45	192	42	0.03	8	1350	26	<5	<20	26	0.02	<10	20	<10	<1	59
QC DATA:																													
Repeat:																													
1	G37761	1.3	1.74	20	35	<5	0.35	1	17	107	992	5.35	<10	1.04	604	518	0.02	6	1300	98	15	<20	34	0.04	<10	41	<10	1	102
11	G37771	1.6	1.59	15	40	<5	0.35	2	19	84	1064	6.10	<10	0.90	464	132	0.02	7	1320	102	10	<20	32	0.03	<10	35	<10	<1	104
19	G37779	0.7	2.04	10	40	<5	0.36	1	16	87	305	5.35	<10	1.22	537	97	0.03	5	1430	44	10	<20	35	0.03	<10	47	<10	1	186
Resplit:																													
1	G37761	1.4	1.66	15	35	<5	0.35	2	16	118	972	5.00	<10	0.95	556	502	0.02	6	1320	98	10	<20	34	0.03	<10	39	<10	1	96
Standard:																													
Pb113		11.3	0.27	40	65	<5	1.71	39	2	5	2289	1.11	<10	0.10	1457	64	0.02	2	80	5438	15	<20	89	0.01	<10	8	<10	<1	6939

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5581S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5582

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

25-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07104
Submitted by; Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35441	0.15	0.004
2	G35442	0.08	0.002
3	G35443	0.11	0.003
4	G35444	0.12	0.003
5	G35445	0.05	0.001
6	G35446	0.10	0.003
7	G35447	0.33	0.010
8	G35448	<0.03	<0.001
9	G35449	0.09	0.003
10	G35450	0.13	0.004
11	G35451	0.10	0.003
12	G35452	0.04	0.001
13	G35453	0.05	0.001
14	G35454	0.14	0.004
15	G35455	0.08	0.002
16	G35456	0.03	0.001
17	G35457	0.99	0.029
18	G35458	0.09	0.003
19	G35459	0.08	0.002
20	G35460	0.06	0.002
21	G35461	0.11	0.003
22	G35462	0.07	0.002
23	G35463	0.07	0.002
24	G35464	0.10	0.003
25	G35465	0.07	0.002
26	G35466	0.10	0.003
27	G35467	0.07	0.002
28	G35468	0.10	0.003

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5582 25-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G35469	0.08	0.002
30	G35470	0.09	0.003
31	G35471	0.10	0.003
32	G35472	0.60	0.017
33	G35473	0.07	0.002
34	G35474	0.11	0.003
35	G35475	0.62	0.018
QC DATA:			
Repeat:			
1	G35441	0.14	0.004
10	G35450	0.12	0.003
19	G35459	0.09	0.003
Standard:			
SI25		1.84	0.054

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

2-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5582

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07104
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35441	3.4	0.98	20	55	<5	1.61	8	18	105	947	2.99	<10	1.16	1324	16	0.06	24	1080	174	15	<20	75	0.13	<10	67	<10	6	479
2	G35442	2.2	1.45	20	75	<5	5.04	7	14	67	820	3.77	<10	1.86	2420	12	0.05	18	810	132	15	<20	398	0.15	<10	96	<10	7	363
3	G35443	2.5	1.24	20	70	<5	2.09	3	18	75	965	3.63	<10	1.52	1680	21	0.04	21	880	130	10	<20	139	0.15	<10	74	<10	9	174
4	G35444	3.2	1.29	25	55	<5	1.88	2	19	68	747	3.46	<10	1.44	1341	15	0.02	21	870	124	25	<20	115	0.16	<10	58	<10	9	149
5	G35445	2.5	2.17	30	85	<5	3.56	7	18	48	1071	3.04	<10	3.33	1453	9	0.03	39	850	440	30	<20	198	0.17	<10	80	<10	7	427
6	G35446	1.8	1.06	20	75	<5	3.33	<1	16	54	883	2.91	<10	1.30	987	7	0.04	13	840	42	<5	<20	316	0.16	<10	62	<10	7	45
7	G35447	11.5	1.89	35	85	<5	3.53	55	26	60	3966	7.51	<10	2.41	2531	27	0.03	22	940	1890	30	<20	291	0.15	<10	104	<10	5	3102
8	G35448	<0.2	1.15	20	255	15	0.69	<1	7	90	10	2.22	<10	0.60	561	<1	0.12	6	900	18	<5	<20	102	0.14	<10	47	<10	4	52
9	G35449	2.8	1.45	30	75	<5	3.15	4	23	76	904	5.31	<10	1.66	2154	8	0.04	22	990	202	15	<20	223	0.18	<10	91	<10	8	293
10	G35450	2.3	1.43	30	65	<5	4.19	7	19	64	1319	3.98	<10	1.68	2001	7	0.05	24	1090	206	15	<20	267	0.18	<10	82	<10	6	387
11	G35451	2.1	1.57	20	60	<5	3.10	1	21	54	1013	3.52	<10	1.96	1529	8	0.04	24	1110	62	30	<20	245	0.17	<10	69	<10	10	81
12	G35452	1.7	1.52	55	90	<5	2.43	12	11	64	274	2.75	10	2.10	1882	9	0.12	16	1220	230	55	<20	147	0.15	<10	75	<10	8	663
13	G35453	1.4	1.49	40	90	<5	5.21	9	10	63	421	2.88	10	2.19	2925	8	0.08	18	1180	314	50	<20	184	0.14	<10	95	<10	7	511
14	G35454	1.6	1.23	45	85	<5	2.80	3	12	70	416	2.55	<10	1.47	1477	9	0.10	21	1120	170	15	<20	162	0.16	<10	74	<10	8	219
15	G35455	2.1	1.08	40	115	<5	4.59	11	11	68	578	3.07	<10	1.14	2546	10	0.08	17	1020	346	20	<20	184	0.13	<10	87	<10	7	680
16	G35456	1.5	0.82	55	70	10	1.70	23	9	94	147	2.33	<10	0.91	1115	46	0.08	23	1250	430	10	<20	69	0.13	<10	79	<10	8	1044
17	G35457	3.8	1.29	65	75	<5	0.78	7	18	57	3314	3.78	20	0.52	286	222	0.03	15	320	146	35	<20	34	0.04	<10	47	<10	6	169
18	G35458	1.8	1.48	50	135	<5	8.65	10	13	60	514	2.30	<10	2.06	2703	11	0.06	15	1020	364	25	<20	515	0.14	<10	89	<10	10	658
19	G35459	3.1	1.49	40	120	<5	2.81	4	17	82	580	2.61	<10	2.05	1778	13	0.11	23	1290	232	25	<20	142	0.16	<10	115	<10	8	290
20	G35460	2.0	1.01	45	105	<5	2.85	7	11	97	157	1.84	<10	1.33	1695	19	0.13	12	1300	386	20	<20	175	0.11	<10	101	<10	6	468
21	G35461	2.1	0.85	50	100	<5	2.08	5	19	115	275	1.50	<10	1.00	1369	20	0.09	23	1180	172	25	<20	90	0.10	<10	90	<10	6	371
22	G35462	2.4	1.11	45	75	<5	1.06	9	9	109	260	1.83	<10	1.53	1447	18	0.07	17	1220	340	40	<20	64	0.12	<10	105	<10	5	578
23	G35463	2.3	0.84	60	90	<5	1.51	8	18	115	325	1.83	<10	1.00	1187	14	0.07	18	1040	326	30	<20	78	0.10	<10	88	<10	6	536
24	G35464	3.4	0.95	65	60	<5	1.51	18	25	96	605	3.19	<10	1.16	1149	26	0.06	25	1240	410	65	<20	75	0.11	<10	80	<10	6	1354
25	G35465	2.6	0.87	35	100	<5	2.20	3	10	102	308	1.53	<10	0.98	1163	29	0.07	15	950	312	10	<20	107	0.11	<10	74	<10	5	282

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35466	3.8	1.18	50	75	<5	1.97	2	10	88	276	1.78	<10	1.46	1225	32	0.07	21	1330	324	10	<20	101	0.12	<10	104	<10	5	186
27	G35467	2.3	1.02	35	80	<5	3.15	<1	10	104	203	1.80	<10	1.18	1281	15	0.08	12	1220	106	10	<20	124	0.12	<10	95	<10	6	68
28	G35468	2.7	1.45	30	75	50	1.81	<1	25	66	350	3.81	<10	1.70	1099	9	0.05	23	1660	72	10	<20	98	0.15	<10	96	<10	11	79
29	G35469	1.9	1.20	40	75	20	4.47	1	19	69	183	3.17	<10	1.29	1493	23	0.06	21	1430	74	20	<20	203	0.14	<10	90	<10	9	99
30	G35470	1.9	0.71	35	65	<5	4.98	<1	20	76	314	2.31	<10	0.72	1179	10	0.07	15	1110	82	5	<20	223	0.12	<10	69	<10	6	43
31	G35471	2.1	0.74	35	65	<5	3.47	<1	22	82	277	2.69	<10	0.75	938	19	0.08	21	1370	52	10	<20	143	0.12	<10	69	<10	6	39
32	G35472	2.6	0.87	30	80	<5	3.68	<1	16	85	285	3.36	<10	0.89	1133	9	0.05	15	1160	48	10	<20	179	0.11	<10	66	<10	4	56
33	G35473	1.8	0.92	55	65	10	1.53	<1	20	83	107	2.29	<10	0.94	692	13	0.07	26	1360	42	20	<20	79	0.12	<10	80	<10	5	41
34	G35474	3.3	0.77	30	60	5	2.71	<1	19	106	188	3.08	<10	0.74	861	8	0.06	16	1120	260	<5	<20	280	0.12	<10	93	<10	3	49
35	G35475	3.5	1.13	50	80	15	2.83	<1	24	82	210	3.99	<10	1.19	1240	7	0.06	26	1710	172	10	<20	128	0.19	<10	87	<10	8	78
QC DATA:																													
Repeat:																													
1	G35441	3.3	0.99	25	65	<5	1.66	8	19	106	927	3.04	<10	1.15	1338	15	0.06	25	1160	186	15	<20	80	0.15	<10	68	<10	9	504
10	G35450	2.3	1.48	30	65	<5	4.34	8	21	68	1303	4.20	<10	1.67	2089	8	0.05	26	1210	234	20	<20	282	0.19	<10	86	<10	6	427
19	G35459	3.1	1.51	45	125	<5	2.88	4	17	86	580	2.66	<10	2.08	1809	13	0.11	23	1350	244	20	<20	140	0.17	<10	119	<10	8	298
Resplit:																													
1	G35441	3.0	1.07	25	50	<5	1.60	10	20	110	913	3.40	<10	1.15	1451	27	0.06	26	1040	176	20	<20	76	0.13	<10	72	<10	7	494
Standard:																													
Pb113		11.5	0.24	55	60	<5	1.63	46	3	7	2342	1.02	<10	0.14	1517	67	0.02	7	150	5438	25	<20	80	<0.01	<10	13	<10	<1	7013

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5582
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5583

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

25-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07105
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37796	0.99	0.029
2	G37797	1.03	0.030
3	G37798	0.56	0.016
4	G37799	0.15	0.004
5	G37800	0.56	0.016
6	G37801	0.24	0.007
7	G37802	0.23	0.007
8	G37803	0.33	0.010
9	G37804	0.27	0.008
10	G37805	0.26	0.008
11	G37806	0.26	0.008
12	G37807	0.18	0.005
13	G37808	0.12	0.003
14	G37809	0.29	0.008
15	G37810	0.15	0.004
16	G37811	0.19	0.006
17	G37812	0.27	0.008
18	G37813	0.30	0.009
19	G37814	0.40	0.012
20	G37815	0.44	0.013
21	G37816	0.36	0.010
22	G37817	0.18	0.005
23	G37818	0.17	0.005
24	G37819	<0.03	<0.001
25	G37820	<0.03	<0.001

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5583 25-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	G37821	0.09	0.003
27	G37822	0.17	0.005
28	G37823	0.10	0.003
29	G37824	0.08	0.002
30	G37825	0.11	0.003
31	G37826	0.28	0.008
32	G37827	0.10	0.003
33	G37828	0.04	0.001
34	G37829	0.05	0.001
35	G37830	0.04	0.001

QC DATA:

Repeat:

1	G37796	0.99	0.029
10	G37805	0.22	0.006
19	G37814	0.40	0.012

Resplits:

1	G37796	0.93	0.027

Standard:

SI25		1.78	0.052

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO-TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

28-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5583

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1


No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07105
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37796	1.7	1.56	<5	40	<5	0.34	1	15	82	1526	5.17	<10	0.90	281	19	0.04	8	1270	30	15	<20	26	0.02	<10	35	<10	1	79
2	G37797	1.8	1.34	<5	45	<5	0.31	2	16	72	1861	5.55	<10	0.74	227	19	0.04	10	1140	28	15	<20	24	0.01	<10	25	<10	<1	64
3	G37798	1.1	0.93	<5	35	<5	0.27	<1	15	75	1361	4.17	<10	0.40	116	18	0.04	11	1000	22	<5	<20	22	0.01	<10	14	<10	<1	35
4	G37799	0.8	0.78	<5	35	<5	0.16	1	17	121	620	4.68	<10	0.32	114	30	0.04	21	550	20	<5	<20	18	0.02	<10	10	<10	<1	26
5	G37800	1.0	1.87	<5	40	<5	0.27	2	22	89	805	5.04	<10	1.14	310	62	0.04	27	1020	32	15	<20	26	0.02	<10	39	<10	<1	80
6	G37801	0.8	0.85	<5	35	<5	0.22	<1	17	124	687	4.12	<10	0.35	98	62	0.04	24	800	22	<5	<20	21	0.01	<10	15	<10	<1	27
7	G37802	0.7	1.34	<5	35	<5	0.23	<1	12	123	714	4.19	<10	0.67	203	27	0.05	18	850	26	<5	<20	24	0.02	<10	22	<10	<1	59
8	G37803	0.7	2.05	<5	50	<5	0.24	3	17	99	766	5.63	<10	1.10	325	48	0.05	32	850	34	30	<20	22	0.01	<10	33	<10	<1	99
9	G37804	0.6	1.33	<5	40	<5	0.21	<1	19	96	536	4.75	<10	0.72	147	33	0.04	25	780	24	<5	<20	19	0.02	<10	24	<10	<1	52
10	G37805	0.7	0.75	<5	35	<5	0.22	1	23	100	403	4.45	<10	0.30	67	47	0.04	22	820	24	<5	<20	22	0.02	<10	12	<10	<1	24
11	G37806	0.6	0.84	<5	35	<5	0.22	2	20	102	496	4.60	<10	0.36	73	37	0.04	23	780	28	10	<20	20	0.01	<10	13	<10	<1	28
12	G37807	0.6	0.97	<5	35	<5	0.32	1	17	78	482	3.69	<10	0.51	125	62	0.04	23	1250	22	10	<20	34	0.01	<10	15	<10	<1	41
13	G37808	1.0	0.81	<5	35	<5	0.29	<1	17	108	527	3.72	<10	0.36	105	26	0.03	20	1070	24	<5	<20	28	0.01	<10	12	<10	<1	30
14	G37809	0.5	1.33	<5	35	<5	0.30	1	22	87	562	5.20	<10	0.79	193	32	0.04	24	1120	28	5	<20	34	0.02	<10	24	<10	<1	56
15	G37810	0.5	1.19	<5	35	<5	0.24	1	27	95	527	4.46	<10	0.65	170	42	0.04	24	930	24	<5	<20	30	0.02	<10	19	<10	<1	46
16	G37811	0.4	1.65	<5	40	<5	0.25	2	24	80	517	5.09	<10	1.00	244	52	0.05	27	930	32	15	<20	33	0.02	<10	27	<10	<1	67
17	G37812	0.6	1.49	<5	40	<5	0.21	1	20	87	770	3.90	<10	0.90	161	44	0.04	29	760	34	10	<20	26	0.01	<10	27	<10	<1	53
18	G37813	0.4	1.47	<5	35	<5	0.32	<1	19	68	663	3.76	<10	0.95	212	69	0.04	25	1240	28	10	<20	29	0.01	<10	24	<10	<1	49
19	G37814	0.5	1.37	<5	40	<5	0.26	1	21	84	989	4.90	<10	0.91	198	52	0.04	18	930	30	10	<20	25	0.02	<10	23	<10	<1	47
20	G37815	0.7	1.33	<5	35	<5	0.30	1	16	64	1105	3.48	<10	0.85	199	28	0.05	16	1100	26	15	<20	31	0.02	<10	22	<10	<1	47
21	G37816	2.7	0.91	30	40	<5	1.42	2	16	94	1653	3.42	10	0.54	548	39	0.01	25	750	228	10	<20	103	0.05	<10	135	<10	7	122
22	G37817	2.6	0.84	<5	45	<5	1.61	2	13	87	861	3.63	10	0.33	539	14	<0.01	19	750	210	<5	<20	132	0.03	<10	115	<10	6	67
23	G37818	1.8	0.68	10	45	<5	2.98	3	9	84	853	2.98	10	0.38	1307	64	0.01	11	800	242	10	<20	216	0.04	<10	76	<10	5	114
24	G37819	<0.2	1.00	5	265	10	0.58	<1	5	90	5	2.09	<10	0.59	534	1	0.13	6	730	20	<5	<20	89	0.11	<10	43	<10	6	43
25	G37820	2.4	1.04	<5	50	<5	3.02	2	12	56	440	3.08	<10	0.76	1355	10	0.01	8	1080	226	10	<20	214	0.07	<10	105	<10	6	86

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37821	2.5	1.22	15	50	<5	4.22	5	11	63	395	2.84	<10	0.99	1884	17	0.01	9	830	446	10	<20	304	0.07	<10	108	<10	4	353
27	G37822	4.7	1.05	10	45	<5	3.71	13	8	59	358	3.16	<10	0.97	1888	13	0.02	7	970	840	5	<20	283	0.07	<10	134	<10	6	865
28	G37823	3.6	0.97	15	40	<5	3.16	12	11	61	513	2.89	<10	0.91	1349	13	0.04	7	1070	880	10	<20	221	0.09	<10	139	<10	5	775
29	G37824	3.7	1.02	10	40	<5	3.31	5	11	49	545	3.24	<10	0.99	1701	26	0.03	7	1030	814	15	<20	231	0.07	<10	111	<10	5	246
30	G37825	3.1	1.00	<5	45	<5	2.68	3	14	60	749	5.42	<10	0.95	1791	30	0.02	10	870	514	15	<20	223	0.07	<10	123	<10	3	119
31	G37826	3.2	1.20	20	45	<5	0.99	2	18	63	2660	3.51	20	0.62	193	209	0.04	10	320	68	10	<20	58	0.04	<10	45	<10	6	270
32	G37827	3.5	0.96	<5	50	<5	2.51	2	16	75	1306	5.26	<10	0.86	1773	29	0.02	11	820	458	15	<20	247	0.08	<10	130	<10	4	76
33	G37828	1.6	1.58	15	110	<5	>10	1	8	34	350	3.25	10	2.00	4946	13	0.01	9	600	270	25	<20	616	0.09	<10	118	<10	10	120
34	G37829	0.9	0.87	15	45	<5	1.65	<1	9	53	274	3.06	10	0.59	704	57	0.04	5	1150	100	5	<20	122	0.06	<10	67	<10	6	63
35	G37830	0.9	1.00	10	40	<5	1.38	<1	10	87	659	3.51	20	0.72	764	41	0.05	7	1120	72	<5	<20	97	0.04	<10	97	<10	5	65
QC DATA:																													
Repeat:																													
1	G37796	1.5	1.65	<5	40	<5	0.35	2	15	86	1571	5.26	<10	0.93	288	18	0.04	8	1290	30	15	<20	31	0.01	<10	36	<10	1	80
10	G37805	0.7	0.79	<5	35	<5	0.23	2	24	104	409	4.56	<10	0.32	68	50	0.04	24	820	24	5	<20	22	0.01	<10	13	<10	<1	25
19	G37814	0.5	1.38	<5	40	<5	0.26	2	22	86	974	4.94	<10	0.90	201	48	0.04	21	950	34	10	<20	25	0.03	<10	23	<10	<1	49
Resplit:																													
1	G37796	1.5	1.61	<5	40	<5	0.34	3	14	78	1566	5.27	<10	0.94	293	20	0.04	11	1250	34	25	<20	28	0.02	<10	36	<10	1	85
Standard:																													
Pb113		11.3	0.28	40	60	<5	1.66	41	2	5	2302	1.03	<10	0.11	1569	65	0.02	4	80	5466	20	<20	88	<0.01	<10	8	<10	<1	6939

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish



ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5578
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5584

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

25-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07106
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37831	0.04	0.001
2	G37832	0.03	0.001
3	G37833	0.08	0.002
4	G37834	0.16	0.005
5	G37835	0.11	0.003
6	G37836	0.13	0.004
7	G37837	0.98	0.029
8	G37838	0.03	0.001
9	G37839	<0.03	<0.001
10	G37840	0.11	0.003
11	G37841	0.06	0.002
12	G37842	0.15	0.004
13	G37843	0.20	0.006
14	G37844	0.31	0.009
15	G37845	0.27	0.008
16	G37846	0.16	0.005
17	G37847	0.10	0.003
18	G37848	0.28	0.008
19	G37849	0.30	0.009
20	G37850	0.05	0.001
21	G37851	0.14	0.004
22	G37852	0.11	0.003
23	G37853	<0.03	<0.001
24	G37854	0.11	0.003
25	G37855	0.11	0.003
26	G37856	0.06	0.002

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5584 25-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	G37857	0.06	0.002
28	G37858	0.16	0.005
29	G37859	0.57	0.017
30	G37860	0.34	0.010
31	G37861	0.46	0.013
32	G37862	0.33	0.010
33	G37863	0.09	0.003
34	G37864	0.09	0.003
35	G37865	0.08	0.002

QC DATA:

Repeat:

1	G37831	0.04	0.001
10	G37840	0.08	0.002
19	G37849	0.24	0.007

Resplits:

1	G37831	0.04	0.001

Standard:

SI25		1.81	0.053

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

28-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5584

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07106
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37831	0.7	1.06	25	45	<5	2.84	4	9	62	258	3.06	10	0.83	1152	26	0.04	7	1180	112	10	<20	147	0.09	<10	77	<10	7	214
2	G37832	1.0	0.84	15	45	<5	1.20	1	11	67	407	2.95	20	0.71	823	49	0.04	7	1170	50	10	<20	88	0.07	<10	60	<10	7	44
3	G37833	1.3	0.72	45	50	<5	1.62	1	11	64	331	2.87	20	0.44	832	56	0.03	6	1190	106	5	<20	146	0.05	<10	54	<10	8	58
4	G37834	5.3	0.56	35	35	<5	1.91	14	11	69	824	3.15	20	0.20	1004	477	0.01	10	1070	1006	15	<20	152	0.04	<10	47	<10	5	1065
5	G37835	3.8	0.58	35	35	<5	1.11	1	11	70	1367	2.90	20	0.18	807	50	0.01	7	1090	136	<5	<20	96	0.04	<10	40	<10	5	69
6	G37836	4.6	0.86	50	45	<5	1.22	<1	12	67	1594	2.96	20	0.43	1108	35	<0.01	8	1110	162	5	<20	106	0.04	<10	61	<10	7	47
7	G37837	3.7	1.08	55	50	<5	0.64	4	15	61	3277	3.79	20	0.48	274	209	0.03	14	280	136	35	<20	31	0.03	<10	41	<10	5	158
8	G37838	3.1	0.97	15	40	<5	1.39	2	11	70	1287	3.04	20	0.55	1316	25	0.02	9	1060	248	5	<20	135	0.05	<10	76	<10	6	199
9	G37839	2.4	1.01	15	45	<5	1.34	2	11	65	1190	2.84	20	0.63	1221	13	0.02	8	1110	102	10	<20	136	0.05	<10	79	<10	6	150
10	G37840	3.4	0.74	5	35	<5	2.41	1	11	49	1043	3.01	20	0.49	1102	22	0.02	4	1210	454	<5	<20	241	0.02	<10	54	<10	5	165
11	G37841	0.9	1.66	<5	40	15	3.73	2	22	100	78	5.53	10	1.76	2143	25	0.03	23	1100	62	15	<20	463	0.04	<10	246	<10	4	128
12	G37842	1.6	1.00	25	35	20	2.90	2	14	99	61	4.32	10	0.95	1509	40	<0.01	14	1220	120	<5	<20	300	0.03	<10	194	<10	4	167
13	G37843	0.6	1.06	15	40	20	2.81	1	22	107	95	5.61	10	0.99	1884	99	0.04	23	1240	50	10	<20	399	0.04	<10	85	<10	3	92
14	G37844	1.0	1.59	15	35	25	3.99	4	15	130	57	5.70	<10	1.54	2426	50	0.03	29	1260	134	15	<20	551	0.04	<10	117	<10	4	290
15	G37845	0.8	1.46	10	40	30	3.00	3	30	101	35	6.50	<10	1.40	1833	32	0.03	35	1320	48	30	<20	419	0.04	<10	108	<10	1	94
16	G37846	0.8	1.39	25	40	15	2.95	3	24	87	36	5.58	<10	1.39	1909	27	0.03	29	1320	40	20	<20	494	0.04	<10	92	<10	2	94
17	G37847	3.0	0.80	40	25	<5	2.32	2	17	86	196	3.71	<10	0.73	721	6	0.01	17	1220	40	75	<20	216	0.02	<10	23	<10	4	96
18	G37848	4.3	0.57	20	30	<5	1.63	2	12	69	188	3.23	<10	0.33	489	4	0.01	7	1360	60	65	<20	142	0.02	<10	18	<10	4	86
19	G37849	20.7	0.29	85	60	<5	1.21	7	17	66	822	9.08	<10	0.03	362	10	<0.01	12	990	122	345	<20	106	0.03	<10	8	<10	<1	209
20	G37850	1.0	0.37	<5	30	<5	1.82	2	14	64	262	3.58	<10	0.24	546	5	0.01	7	1310	34	20	<20	149	0.02	<10	13	<10	3	42
21	G37851	1.2	0.42	20	25	<5	2.18	2	13	73	322	3.24	<10	0.33	606	38	0.02	5	1280	58	25	<20	192	0.02	<10	16	<10	3	60
22	G37852	2.8	0.32	30	35	<5	1.89	3	14	72	406	3.91	<10	0.14	528	11	0.01	8	1260	32	70	<20	151	0.03	<10	9	<10	2	44
23	G37853	<0.2	0.93	10	260	10	0.57	<1	6	111	4	1.92	<10	0.55	496	4	0.10	7	770	20	5	<20	98	0.09	<10	42	<10	4	40
24	G37854	0.8	0.39	<5	25	<5	2.01	1	15	74	332	3.41	<10	0.59	718	56	0.02	6	1280	32	15	<20	213	0.02	<10	13	<10	3	42
25	G37855	2.1	0.40	20	30	<5	1.44	1	18	73	594	3.44	<10	0.50	662	23	0.01	7	1330	28	20	<20	126	0.02	<10	12	<10	4	61

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37856	8.0	0.37	85	35	<5	1.51	4	14	88	493	3.44	<10	0.58	748	33	<0.01	8	1180	48	85	<20	110	0.01	<10	11	<10	3	100
27	G37857	3.3	0.41	40	30	<5	1.97	1	13	69	398	3.01	<10	0.74	808	27	0.02	2	1330	40	25	<20	167	0.02	<10	13	<10	4	72
28	G37858	1.3	0.50	10	30	<5	1.23	<1	15	69	435	3.34	<10	0.65	462	9	0.02	6	1280	22	5	<20	185	0.02	<10	16	<10	3	23
29	G37859	2.2	0.81	<5	30	<5	1.37	1	17	76	653	3.93	<10	1.07	704	48	0.02	7	1290	30	15	<20	175	0.02	<10	35	<10	4	41
30	G37860	1.4	0.87	<5	35	<5	1.01	1	16	55	717	3.91	<10	0.96	443	48	0.03	7	1260	32	15	<20	130	0.02	<10	42	<10	3	30
31	G37861	1.2	0.81	15	30	<5	1.06	<1	13	59	568	3.41	<10	0.86	475	168	0.03	5	1260	34	<5	<20	146	0.02	<10	39	<10	4	33
32	G37862	1.3	1.04	10	35	<5	1.33	1	13	46	445	3.54	<10	1.11	624	16	0.03	6	1380	32	15	<20	179	0.02	<10	46	<10	3	65
33	G37863	1.6	0.95	<5	35	<5	1.31	2	19	59	623	4.08	<10	1.03	676	83	0.02	7	1300	48	15	<20	169	0.02	<10	44	<10	3	80
34	G37864	2.1	0.68	15	25	<5	1.34	1	16	66	663	3.93	<10	0.86	592	24	0.02	7	1310	46	20	<20	238	0.02	<10	25	<10	2	67
35	G37865	1.0	0.92	15	35	<5	1.59	<1	14	67	499	3.00	<10	1.05	750	26	0.02	6	1280	32	10	<20	215	0.03	<10	41	<10	4	45
QC DATA:																													
Repeat:																													
1	G37831	0.9	1.21	10	50	<5	2.86	4	10	68	253	3.09	10	0.84	1158	27	0.05	7	1190	108	15	<20	147	0.09	<10	91	<10	8	218
10	G37840	3.5	0.83	15	40	<5	2.40	1	11	53	1023	3.06	20	0.51	1102	23	0.02	2	1230	472	<5	<20	239	0.02	<10	63	<10	6	168
19	G37849	20.3	0.30	90	55	<5	1.25	7	16	74	811	8.48	<10	0.04	372	9	0.01	11	1040	126	345	<20	108	0.02	<10	10	<10	<1	211
Resplit:																													
1	G37831	0.8	1.09	20	45	<5	2.88	1	11	55	275	3.15	20	0.84	1174	30	0.04	7	1220	126	15	<20	146	0.09	<10	84	<10	9	219
Standard:																													
Pb113		11.6	0.26	40	55	<5	1.65	42	2	6	2274	1.07	<10	0.10	1446	60	0.02	9	90	5482	20	<20	81	<0.01	<10	10	<10	<1	7057

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5578
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5585

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

28-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07107
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37866	0.10	0.003
2	G37867	0.06	0.002
3	G37868	0.10	0.003
4	G37869	0.23	0.007
5	G37870	0.18	0.005
6	G37871	0.27	0.008
7	G37872	0.17	0.005
8	G37873	0.14	0.004
9	G37874	0.23	0.007
10	G37875	0.16	0.005
11	G37876	0.21	0.006
12	G37877	0.29	0.008
13	G37878	0.21	0.006
14	G37879	0.28	0.008
15	G37880	<0.03	<0.001
16	G37881	0.25	0.007
17	G37882	0.24	0.007
18	G37883	0.27	0.008
19	G37884	0.14	0.004
20	G37885	0.26	0.008
21	G37886	1.88	0.055
22	G37887	0.21	0.006
23	G37888	0.35	0.010
24	G37889	0.47	0.014
25	G37890	0.21	0.006
26	G37891	0.50	0.015
27	G37892	0.20	0.006
28	G37893	0.22	0.006

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5585 28-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G37894	1.68	0.049
30	G37895	0.52	0.015
31	G37896	0.41	0.012
32	G37897	1.26	0.037
33	G37898	0.27	0.008
34	G37899	0.46	0.013
35	G37900	0.40	0.012

QC DATA:

Repeat:

1	G37866	0.11	0.003
10	G37875	0.17	0.005
19	G37884	0.14	0.004
24	G37889	0.47	0.014
26	G37891	0.51	0.015
29	G37894	1.63	0.048
32	G37897	1.27	0.037

Resplits:

1	G37866	0.10	0.003

Standard:

SI25		1.82	0.053

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

28-Sep-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5585

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07107
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37866	12.9	0.73	130	25	<5	1.63	4	18	64	1240	4.20	<10	0.89	968	79	0.01	5	1230	142	345	<20	147	0.02	<10	32	<10	4	224
2	G37867	1.1	0.89	10	30	<5	1.31	1	14	54	623	3.15	<10	1.03	759	29	<0.01	4	1380	40	35	<20	108	0.02	<10	42	<10	4	64
3	G37868	0.7	0.98	5	35	<5	1.56	<1	16	55	603	3.65	<10	1.13	787	68	0.02	4	1340	30	10	<20	202	0.02	<10	42	<10	4	52
4	G37869	2.8	0.71	35	30	<5	1.79	2	16	52	528	4.14	<10	0.86	876	177	0.01	4	1350	48	45	<20	223	0.03	<10	28	<10	4	62
5	G37870	1.1	0.89	15	35	<5	1.52	2	17	63	575	4.12	<10	1.15	723	31	0.02	5	1350	36	15	<20	247	0.03	<10	35	<10	4	85
6	G37871	5.2	0.69	40	30	<5	1.52	2	16	63	865	4.03	<10	0.89	750	96	0.02	4	1230	30	45	<20	198	0.02	<10	23	<10	3	53
7	G37872	1.4	0.98	10	35	<5	1.13	<1	16	49	657	3.88	<10	1.10	586	56	0.02	4	1380	38	5	<20	152	0.02	<10	43	<10	4	54
8	G37873	1.8	0.95	<5	30	<5	1.12	5	17	70	791	5.06	<10	1.01	777	54	0.02	7	1270	62	20	<20	111	0.02	<10	42	<10	2	212
9	G37874	2.7	1.10	<5	35	<5	1.47	1	20	60	983	5.45	<10	1.39	1051	31	0.02	6	1250	68	10	<20	125	0.03	<10	41	<10	3	74
10	G37875	1.1	1.22	<5	35	<5	1.10	1	23	57	837	4.99	<10	1.18	664	25	0.03	6	1310	54	5	<20	151	0.03	<10	45	<10	3	49
11	G37876	1.0	1.20	10	40	<5	0.98	1	21	62	785	4.68	<10	1.17	618	27	0.03	5	1360	38	10	<20	118	0.03	<10	44	<10	4	48
12	G37877	3.7	0.99	10	35	<5	1.16	2	17	81	943	4.12	<10	1.02	743	115	0.02	5	1280	48	15	<20	136	0.02	<10	37	<10	3	76
13	G37878	2.4	0.84	10	30	<5	1.10	1	17	68	946	4.15	<10	0.84	735	53	0.01	5	1320	34	25	<20	95	0.02	<10	32	<10	3	52
14	G37879	19.5	0.64	105	30	<5	1.16	5	14	65	979	3.99	<10	0.60	863	44	<0.01	5	1210	184	290	<20	82	0.03	<10	22	<10	3	389
15	G37880	0.9	1.03	15	275	10	0.64	<1	7	90	8	2.02	<10	0.56	543	3	0.12	5	800	26	15	<20	96	0.12	<10	45	<10	3	44
16	G37881	6.9	1.74	20	395	<5	1.25	2	15	53	769	4.36	<10	0.98	1046	63	0.03	5	1310	76	30	<20	110	0.04	<10	49	<10	3	86
17	G37882	6.4	0.53	15	35	<5	0.94	5	16	75	1010	5.31	<10	0.41	734	97	<0.01	5	1150	112	10	<20	74	0.03	<10	17	<10	1	149
18	G37883	1.9	1.01	15	35	<5	1.33	<1	12	49	437	3.31	<10	0.86	1024	39	0.02	3	1400	46	5	<20	128	0.02	<10	35	<10	3	85
19	G37884	2.3	1.11	10	35	<5	0.97	1	16	45	544	3.54	<10	0.93	645	29	0.02	4	1460	44	10	<20	85	0.02	<10	37	<10	3	82
20	G37885	4.6	1.13	10	35	<5	1.54	2	12	60	939	3.61	<10	1.14	1029	74	0.02	4	1350	52	20	<20	117	0.03	<10	40	<10	3	93
21	G37886	4.1	1.18	35	45	<5	1.03	2	22	55	8709	4.15	<10	0.58	202	612	0.05	65	<10	68	20	<20	60	0.03	<10	44	<10	4	71
22	G37887	2.6	1.20	15	25	<5	1.39	2	14	56	525	3.76	<10	1.14	950	47	0.02	5	1400	36	10	<20	97	0.02	<10	39	<10	3	106
23	G37888	9.1	0.84	25	35	<5	1.37	3	16	58	1230	4.44	<10	0.70	1010	71	<0.01	6	1290	128	15	<20	80	0.03	<10	27	<10	2	135
24	G37889	9.3	0.34	115	35	<5	0.63	2	18	77	1696	4.42	<10	0.02	243	79	0.01	7	1140	68	155	<20	58	0.02	<10	10	<10	1	90
25	G37890	6.3	0.56	85	30	<5	2.92	2	13	68	768	3.29	<10	0.40	1827	57	<0.01	8	1120	80	120	<20	278	0.03	<10	19	<10	2	97

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37891	14.3	0.31	120	10	<5	2.17	3	12	67	613	3.44	<10	0.08	626	80	<0.01	7	1060	92	165	<20	437	0.02	<10	10	<10	<1	82
27	G37892	1.5	0.80	20	20	<5	2.72	1	12	55	569	3.09	<10	0.73	1411	45	<0.01	6	1110	36	10	<20	406	0.03	<10	27	<10	2	114
28	G37893	1.7	0.81	10	25	<5	2.37	2	13	73	939	3.41	<10	0.65	1103	47	<0.01	7	1060	78	<5	<20	260	0.02	<10	25	<10	1	151
29	G37894	4.5	0.58	40	15	<5	1.87	4	14	56	868	3.66	<10	0.40	1083	47	<0.01	11	1020	130	35	<20	193	0.01	<10	19	<10	1	189
30	G37895	5.1	0.48	75	15	<5	1.85	2	11	85	783	3.37	<10	0.29	840	66	<0.01	6	750	64	60	<20	328	0.02	<10	16	<10	<1	88
31	G37896	19.5	0.36	245	25	<5	1.35	5	14	70	1240	4.18	<10	0.11	421	73	0.01	7	910	88	430	<20	188	0.02	<10	11	<10	<1	201
32	G37897	8.5	0.50	75	20	<5	1.94	2	13	69	968	3.66	<10	0.28	776	89	0.01	7	980	72	95	<20	280	0.02	<10	16	<10	<1	90
33	G37898	1.7	0.83	15	35	<5	2.42	1	12	56	707	2.94	<10	0.65	1086	81	0.02	6	940	30	10	<20	275	0.02	<10	25	<10	1	85
34	G37899	3.1	0.77	30	25	<5	1.97	1	15	61	864	3.73	<10	0.61	1515	45	0.01	5	1120	40	30	<20	268	0.03	<10	25	<10	1	121
35	G37900	1.7	0.82	25	25	<5	2.19	2	16	58	943	4.03	<10	0.62	1253	88	0.01	5	1290	40	10	<20	332	0.03	<10	25	<10	1	104
QC DATA:																													
Repeat:																													
1	G37866	12.9	0.71	135	30	<5	1.64	5	17	62	1255	4.20	<10	0.89	970	77	<0.01	5	1220	142	340	<20	153	0.02	<10	31	<10	4	228
10	G37875	1.2	1.22	5	35	<5	1.12	2	24	55	857	5.08	<10	1.22	677	29	0.03	8	1330	52	5	<20	157	0.02	<10	45	<10	3	49
19	G37884	2.3	1.06	5	30	<5	0.98	2	16	44	534	3.53	<10	0.91	644	29	0.01	4	1480	42	10	<20	83	0.02	<10	36	<10	3	82
Resplit:																													
1	G37866	11.3	0.82	125	30	<5	1.59	3	17	66	1277	4.05	<10	1.03	981	81	0.01	6	1310	132	330	<20	145	0.03	<10	37	<10	5	224
Standard:																													
Pb113		11.2	0.26	40	65	<5	1.65	38	2	5	2328	1.07	<10	0.10	1495	61	0.02	2	80	5496	20	<20	83	0.01	<10	8	<10	<1	6916

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5581
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5586

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

28-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 070108
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37901	0.33	0.010
2	G37902	0.33	0.010
3	G37903	0.24	0.007
4	G37904	0.33	0.010
5	G37905	0.59	0.017
6	G37906	0.63	0.018
7	G37907	0.60	0.017
8	G37908	0.34	0.010
9	G37909	0.56	0.016
10	G37910	1.06	0.031
11	G37911	0.41	0.012
12	G37912	0.43	0.013
13	G37913	0.37	0.011
14	G37914	0.31	0.009
15	G37915	0.45	0.013
16	G37916	0.56	0.016
17	G37917	0.63	0.018
18	G37918	0.40	0.012
19	G37919	0.32	0.009
20	G37920	0.30	0.009
21	G37921	0.66	0.019
22	G37922	0.44	0.013
23	G37923	0.33	0.010
24	G37924	0.17	0.005
25	G37925	0.83	0.024
26	G37926	0.77	0.022
27	G37927	0.54	0.016
28	G37928	0.30	0.009

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5586 28-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G37929	0.30	0.009
30	G37930	0.45	0.013
31	G37931	0.49	0.014
32	G37932	<0.03	<0.001
33	G37933	0.44	0.013
34	G37934	0.31	0.009
35	G37935	0.26	0.008

QC DATA:

Repeat:

1	G37901	0.34	0.010
10	G37910	1.02	0.030
19	G37919	0.38	0.011

Resplits:

1	G37901	0.32	0.009

Standard:

SI25		1.81	0.053

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

2-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5586

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 070108
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37901	2.1	0.61	20	15	<5	2.48	10	14	65	782	3.60	<10	0.47	1116	41	0.01	5	1180	90	<5	<20	393	0.02	<10	19	<10	<1	403
2	G37902	1.6	0.73	15	25	<5	2.24	2	15	84	635	4.26	<10	0.72	888	50	0.01	14	1150	68	15	<20	313	0.02	<10	19	<10	<1	116
3	G37903	1.1	0.48	<5	30	<5	1.82	2	15	59	554	4.36	<10	0.45	621	52	<0.01	4	1180	48	10	<20	331	0.02	<10	12	<10	<1	58
4	G37904	1.2	0.64	<5	25	<5	2.12	3	17	65	797	4.15	<10	0.66	657	73	<0.01	6	1200	58	15	<20	389	0.02	<10	17	<10	<1	55
5	G37905	2.4	1.08	10	20	<5	2.32	3	23	64	530	5.41	<10	1.06	982	88	<0.01	8	1550	106	15	<20	399	0.03	<10	31	<10	<1	87
6	G37906	2.5	1.10	10	35	<5	2.83	2	21	78	533	5.45	<10	1.07	902	76	<0.01	7	1600	116	15	<20	434	0.03	<10	31	<10	<1	98
7	G37907	2.2	0.96	<5	25	<5	2.04	3	18	61	701	5.24	<10	0.83	922	61	<0.01	5	1380	80	5	<20	337	0.03	<10	25	<10	<1	88
8	G37908	2.2	0.52	<5	30	<5	2.23	2	19	79	570	5.98	<10	0.45	773	172	<0.01	5	1460	56	<5	<20	361	0.03	<10	14	<10	<1	80
9	G37909	1.9	0.75	10	35	<5	1.19	2	28	73	645	6.40	<10	0.65	895	73	<0.01	9	1510	62	10	<20	87	0.03	<10	20	<10	<1	96
10	G37910	2.7	1.07	30	30	<5	1.98	2	18	80	657	5.61	<10	0.92	868	66	<0.01	6	1450	64	10	<20	423	0.03	<10	28	<10	<1	103
11	G37911	1.5	1.51	15	25	<5	3.09	1	16	89	428	4.98	<10	1.30	723	69	<0.01	6	1390	46	15	<20	720	0.03	<10	36	<10	<1	162
12	G37912	1.4	2.01	25	40	<5	0.38	<1	19	69	920	5.83	<10	1.49	566	49	<0.01	5	1520	48	10	<20	33	0.03	<10	43	<10	<1	197
13	G37913	1.8	1.50	15	40	<5	0.40	2	18	70	850	6.41	<10	1.04	421	69	0.01	5	1600	54	5	<20	17	0.03	<10	30	<10	<1	113
14	G37914	1.7	1.54	10	40	<5	0.49	2	19	55	887	7.41	<10	0.98	458	40	0.01	5	2010	58	<5	<20	15	0.03	<10	36	<10	<1	118
15	G37915	1.2	2.02	<5	45	<5	0.44	3	23	57	1038	6.93	<10	1.39	598	49	0.01	11	1790	64	20	<20	18	0.03	<10	48	<10	<1	153
16	G37916	1.1	1.66	<5	50	<5	0.59	3	24	76	769	6.91	<10	1.21	471	113	0.01	7	2430	88	10	<20	15	0.03	<10	60	<10	<1	141
17	G37917	1.1	1.89	<5	50	<5	0.55	2	26	57	983	7.60	<10	1.31	508	78	0.02	8	2230	68	15	<20	18	0.03	<10	64	<10	<1	163
18	G37918	1.1	1.42	<5	40	<5	0.46	2	24	80	1061	7.32	<10	0.91	319	75	0.02	9	1840	60	15	<20	18	0.03	<10	48	<10	<1	100
19	G37919	1.2	1.24	<5	45	<5	0.58	2	29	84	796	8.26	<10	0.70	279	101	0.02	9	2350	78	<5	<20	28	0.03	<10	38	<10	<1	78
20	G37920	1.0	2.23	5	45	<5	0.57	3	25	66	818	8.62	<10	1.45	490	50	0.03	9	2340	74	15	<20	23	0.04	<10	85	<10	<1	121
21	G37921	0.8	1.87	<5	40	<5	0.51	2	24	51	984	7.00	<10	1.18	387	91	0.03	8	2070	58	15	<20	23	0.03	<10	66	<10	<1	109
22	G37922	0.9	1.21	<5	40	<5	0.58	3	22	90	624	7.97	<10	0.57	211	83	0.03	8	2350	60	<5	<20	25	0.03	<10	36	<10	<1	86
23	G37923	1.3	1.27	<5	65	<5	0.64	5	23	70	778	>10	<10	0.50	207	53	0.02	12	2580	78	<5	<20	30	0.05	<10	34	<10	<1	106
24	G37924	1.2	0.88	5	50	<5	0.71	2	21	91	996	6.67	<10	0.27	118	51	0.03	10	2880	42	<5	<20	34	0.03	<10	27	<10	1	64
25	G37925	1.3	1.78	<5	40	<5	0.62	<1	17	63	1048	7.33	<10	0.65	266	59	0.04	<1	2220	<2	<5	<20	22	0.06	<10	56	<10	<1	160

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37926	1.2	0.92	<5	35	<5	0.71	8	25	75	1205	7.48	<10	0.32	121	179	0.06	29	2900	32	95	<20	36	<0.01	<10	45	<10	<1	76
27	G37927	1.4	0.53	<5	40	<5	0.39	2	23	87	1091	7.82	<10	0.07	52	51	0.05	8	1520	34	<5	<20	30	0.03	<10	18	<10	<1	45
28	G37928	3.2	1.19	35	45	<5	0.99	3	21	53	2706	3.67	10	0.68	194	188	0.04	8	390	68	10	<20	57	0.04	<10	46	<10	5	273
29	G37929	0.9	0.57	10	30	<5	0.47	1	24	102	1062	6.01	<10	0.08	52	141	0.06	8	1860	28	<5	<20	43	0.02	<10	19	<10	1	43
30	G37930	1.4	0.51	5	35	<5	0.62	2	17	78	833	5.74	<10	0.03	43	66	0.06	7	2570	34	<5	<20	97	0.02	<10	12	<10	<1	61
31	G37931	1.2	0.45	5	50	<5	0.54	2	16	73	756	5.48	<10	0.02	50	36	0.05	7	2230	54	<5	<20	109	0.03	<10	14	<10	<1	72
32	G37932	<0.2	0.98	20	280	10	0.62	<1	7	90	6	2.29	<10	0.55	543	3	0.11	5	820	20	<5	<20	90	0.11	<10	45	<10	2	46
33	G37933	1.1	0.47	<5	35	<5	0.68	3	16	88	708	5.89	<10	0.03	63	43	0.05	8	2850	66	<5	<20	124	0.02	<10	12	<10	<1	143
34	G37934	0.9	0.43	10	50	<5	0.50	1	13	63	560	4.79	<10	0.01	43	20	0.05	4	2110	60	<5	<20	76	0.02	<10	8	<10	<1	94
35	G37935	1.0	0.33	<5	30	<5	0.32	3	14	80	459	5.94	<10	<0.01	37	40	0.04	5	1290	74	<5	<20	49	0.02	<10	7	<10	<1	233
QC DATA:																													
Repeat:																													
1	G37901	2.2	0.60	20	30	<5	2.25	9	14	64	771	3.57	<10	0.46	1101	47	0.01	6	1170	90	<5	<20	383	0.02	<10	19	<10	1	401
10	G37910	2.5	1.07	25	35	<5	1.76	2	18	76	670	5.58	<10	0.92	863	64	<0.01	7	1430	64	10	<20	402	0.03	<10	28	<10	<1	101
19	G37919	1.3	1.22	<5	45	<5	0.58	2	29	81	795	8.22	<10	0.69	275	93	0.02	9	2330	80	5	<20	22	0.04	<10	37	<10	<1	77
Resplit:																													
1	G37901	2.0	0.65	15	20	<5	2.26	7	15	60	726	3.86	<10	0.49	997	54	0.01	6	1240	80	5	<20	390	0.02	<10	21	<10	<1	356
Standard:																													
Pb113		11.2	0.26	45	55	<5	1.69	41	2	5	2346	1.10	<10	0.10	1422	64	0.02	6	90	5530	20	<20	83	<0.01	<10	10	<10	<1	6960

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5581
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5587

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

28-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07109
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37936	0.20	0.006
2	G37937	0.18	0.005
3	G37938	0.46	0.013
4	G37939	0.52	0.015
5	G37940	0.37	0.011
6	G37941	0.25	0.007
7	G37942	0.51	0.015
8	G37943	0.27	0.008
9	G37944	0.59	0.017
10	G37945	0.58	0.017
11	G37946	0.54	0.016
12	G37947	<0.03	<0.001
13	G37948	0.41	0.012
14	G37949	0.33	0.010
15	G37950	0.31	0.009
16	G37951	0.51	0.015
17	G37952	0.63	0.018
18	G37953	0.38	0.011
19	G37954	0.44	0.013
20	G37955	0.45	0.013
21	G37956	0.58	0.017
22	G37957	0.91	0.027
23	G37958	0.87	0.025
24	G37959	1.06	0.031
25	G37960	1.06	0.031
26	G37961	1.42	0.041
27	G37962	0.78	0.023

ECOTECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5587 28-Sep-07

ET #	Tag #	Au (g/t)	Au (oz/t)
28	G37963	1.23	0.036
29	G37964	0.68	0.020
30	G37965	0.77	0.022
31	G37966	1.10	0.032
32	G37967	0.74	0.022
33	G37968	0.43	0.013
34	G37969	0.64	0.019
35	G37970	0.47	0.014

QC DATA:

Repeat:

1	G37936	0.21	0.006
10	G37945	0.54	0.016
19	G37954	0.45	0.013
22	G37957	0.93	0.027
23	G37958	0.84	0.024
26	G37961	1.29	0.038
28	G37963	1.15	0.034
31	G37970	0.96	0.028

Resplits:

1	G37936	0.21	0.006

Standard:

SI25		1.78	0.052

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

1-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5587

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07109
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37936	0.8	0.34	<5	30	<5	0.18	2	13	90	474	5.22	<10	0.01	32	30	0.04	4	700	58	<5	<20	27	0.02	<10	6	<10	<1	193
2	G37937	1.1	0.36	<5	35	<5	0.36	3	15	78	796	5.68	<10	<0.01	33	69	0.05	6	1460	70	<5	<20	30	0.02	<10	9	<10	<1	183
3	G37938	1.1	0.39	<5	50	<5	0.34	2	14	87	554	5.15	<10	<0.01	37	41	0.04	5	1410	46	<5	<20	33	0.02	<10	9	<10	<1	90
4	G37939	1.0	0.29	<5	40	<5	0.26	2	18	78	633	5.92	<10	<0.01	38	30	0.04	7	1050	36	<5	<20	29	0.02	<10	8	<10	<1	83
5	G37940	0.8	0.58	<5	30	<5	0.27	2	12	86	637	4.89	<10	0.16	103	32	0.03	5	1080	46	<5	<20	30	0.02	<10	10	<10	<1	162
6	G37941	1.1	0.53	<5	35	<5	0.14	5	12	98	515	5.40	<10	0.13	72	44	0.04	16	470	56	45	<20	20	<0.01	<10	11	<10	<1	107
7	G37942	1.0	0.49	<5	40	<5	0.16	3	14	62	628	5.08	<10	0.11	68	25	0.03	4	690	28	<5	<20	23	0.02	<10	8	<10	<1	94
8	G37943	1.0	0.85	<5	55	<5	0.24	3	12	90	583	5.50	<10	0.30	145	23	0.03	4	1150	36	<5	<20	22	0.03	<10	14	<10	<1	206
9	G37944	1.4	0.39	<5	30	<5	0.15	5	13	67	543	5.27	<10	0.07	51	72	0.02	4	660	76	<5	<20	24	0.02	<10	8	<10	<1	404
10	G37945	1.0	0.35	<5	30	<5	0.24	2	12	69	542	4.46	<10	0.02	36	28	0.02	3	1160	52	<5	<20	34	0.02	<10	7	<10	<1	157
11	G37946	1.2	0.36	<5	40	<5	0.27	3	12	67	555	4.54	<10	0.02	39	40	0.02	6	1310	48	<5	<20	43	0.02	<10	8	<10	<1	121
12	G37947	<0.2	1.00	5	255	<5	0.58	<1	6	94	5	2.07	<10	0.63	526	3	0.12	5	920	12	<5	<20	98	0.12	<10	47	<10	5	43
13	G37948	1.1	0.34	<5	30	<5	0.13	3	11	74	391	4.85	<10	0.02	31	166	0.02	4	570	46	<5	<20	21	0.02	<10	7	<10	<1	207
14	G37949	1.0	0.35	<5	30	<5	0.15	1	13	75	532	4.48	<10	0.02	36	14	0.02	3	710	30	<5	<20	26	0.02	<10	7	<10	<1	67
15	G37950	1.1	0.36	<5	25	<5	0.23	3	12	71	483	4.55	<10	0.03	45	61	0.02	4	1100	38	<5	<20	35	0.02	<10	7	<10	<1	183
16	G37951	1.0	0.42	<5	30	<5	0.23	3	12	75	568	4.45	<10	0.05	54	40	0.03	3	1130	28	<5	<20	36	0.02	<10	8	<10	<1	198
17	G37952	1.1	0.45	<5	35	<5	0.16	1	12	61	610	4.67	<10	0.07	58	35	0.02	4	780	26	<5	<20	27	0.02	<10	9	<10	<1	72
18	G37953	0.8	0.34	<5	35	<5	0.13	1	15	56	408	5.41	<10	0.03	36	44	0.02	4	580	22	<5	<20	24	0.03	<10	7	<10	<1	35
19	G37954	1.1	0.45	<5	40	<5	0.16	1	13	75	438	4.62	<10	0.06	44	40	0.02	5	720	22	<5	<20	21	0.02	<10	9	<10	<1	120
20	G37955	1.4	0.44	<5	40	<5	0.16	3	14	91	676	5.50	<10	0.06	44	97	0.02	7	750	26	<5	<20	12	0.02	<10	14	<10	<1	423
21	G37956	1.6	0.32	<5	35	<5	0.19	6	15	82	632	4.93	<10	0.03	42	121	0.02	6	880	24	<5	<20	20	0.02	<10	11	<10	<1	830
22	G37957	2.6	0.32	<5	35	<5	0.30	3	20	69	977	5.29	<10	0.02	53	112	0.02	9	1470	32	<5	<20	49	0.02	<10	13	<10	<1	208
23	G37958	2.5	0.37	<5	45	<5	0.31	2	17	58	850	4.51	<10	0.05	70	90	0.02	6	1560	48	<5	<20	40	0.02	<10	13	<10	<1	228
24	G37959	3.6	1.10	60	70	<5	0.65	3	14	57	3265	3.58	20	0.50	250	203	0.03	13	370	122	30	<20	25	0.03	<10	43	<10	5	156
25	G37960	2.5	0.23	<5	35	<5	0.27	2	15	43	672	3.69	<10	<0.01	54	64	0.02	5	1360	36	<5	<20	32	0.02	<10	8	<10	<1	190

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37961	2.3	0.14	<5	30	<5	0.16	3	14	36	726	3.41	<10	<0.01	28	78	0.01	4	740	22	<5	<20	10	0.01	<10	6	<10	<1	304
27	G37962	1.9	0.19	5	30	<5	0.20	3	13	32	605	3.46	<10	0.02	39	92	0.01	3	990	24	<5	<20	12	0.02	<10	8	<10	<1	380
28	G37963	2.7	1.72	25	160	<5	0.53	2	20	57	1080	6.85	<10	0.68	344	114	0.03	6	2700	46	<5	<20	17	0.04	<10	58	<10	<1	212
29	G37964	1.9	2.79	5	50	<5	0.39	2	18	54	873	7.11	<10	1.42	727	102	0.02	8	1990	58	5	<20	15	0.04	<10	83	<10	<1	346
30	G37965	2.2	1.80	15	50	<5	0.53	1	16	60	885	5.26	<10	0.83	467	144	0.03	4	2760	52	<5	<20	16	0.03	<10	51	<10	<1	201
31	G37966	2.8	2.00	10	40	<5	0.48	<1	19	60	1052	6.12	<10	0.92	578	121	0.02	5	2490	52	<5	<20	13	0.03	<10	54	<10	<1	240
32	G37967	1.8	3.90	25	50	<5	0.32	1	20	52	930	8.66	<10	1.83	1344	125	0.02	6	1630	60	15	<20	12	0.05	<10	104	<10	<1	516
33	G37968	2.3	2.17	10	40	<5	0.44	4	18	61	675	6.17	<10	1.13	861	74	0.02	8	2220	228	15	<20	15	0.03	<10	60	<10	<1	337
34	G37969	2.0	2.17	<5	40	<5	0.36	1	16	55	664	6.09	<10	1.30	1099	62	0.01	6	1840	96	<5	<20	12	0.04	<10	48	<10	<1	305
35	G37970	1.4	2.56	15	45	<5	0.29	2	17	50	687	5.21	<10	1.61	1297	58	0.01	7	1420	92	15	<20	11	0.03	<10	60	<10	<1	345
QC DATA:																													
Repeat:																													
1	G37936	0.9	0.34	<5	25	<5	0.16	3	11	82	447	5.26	<10	0.03	30	27	0.04	4	760	50	<5	<20	22	0.02	<10	7	<10	<1	178
10	G37945	1.0	0.32	<5	30	<5	0.25	2	12	68	543	4.51	<10	0.01	36	28	0.02	4	1200	52	<5	<20	36	0.02	<10	7	<10	<1	161
19	G37954	1.0	0.43	<5	30	<5	0.15	1	13	73	450	4.66	<10	0.05	44	41	0.02	4	720	22	<5	<20	20	0.02	<10	8	<10	<1	127
Resplit:																													
1	G37936	0.8	0.31	<5	30	<5	0.15	2	11	85	453	5.20	<10	0.02	31	34	0.04	5	740	56	<5	<20	27	0.02	<10	6	<10	<1	190
Standard:																													
Pb113		11.6	0.25	45	55	<5	1.61	35	2	5	2173	1.06	<10	0.10	1513	61	0.02	2	90	5402	20	<20	86	0.01	<10	8	<10	<1	6991

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5581
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5588

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

27-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 070110
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35251	0.88	0.026
2	G35252	1.26	0.037
3	G35253	0.79	0.023
4	G35254	0.85	0.025
5	G35255	1.85	0.054
6	G35256	0.27	0.008
7	G35257	0.37	0.011
8	G35258	0.31	0.009
9	G35259	0.21	0.006
10	G35260	0.16	0.005
11	G35261	0.18	0.005
12	G35262	0.19	0.006
13	G35263	0.80	0.023
14	G35264	0.89	0.026
15	G35265	0.49	0.014
16	G35266	0.74	0.022
17	G35267	0.33	0.010
18	G35268	0.64	0.019
19	G35269	0.43	0.013
20	G35270	0.82	0.024
21	G35271	0.47	0.014
22	G35272	0.96	0.028
23	G35273	0.77	0.022
24	G35274	0.65	0.019
25	G35275	0.89	0.026
26	G35276	0.27	0.008
27	G35277	0.81	0.024
28	G35278	0.91	0.027

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5588 27-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G35279	1.08	0.031
30	G35280	0.86	0.025
31	G35281	0.70	0.020
32	G35282	0.74	0.022
33	G35283	1.17	0.034
34	G35284	3.00	0.087
35	G35285	<0.03	<0.001

QC DATA:

Repeat:

1	G35251	0.85	0.025
2	G35252	1.34	0.039
10	G35260	0.16	0.005
19	G35269	0.46	0.013
29	G35279	0.92	0.027
33	G35283	1.33	0.039
34	G35284	2.81	0.082

Resplits:

1	G35251	0.94	0.027

Standard:

SI25		1.82	0.053

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

1-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5588

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 070110
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35251	2.1	0.12	30	30	<5	0.26	<1	10	238	2119	4.99	<10	<0.01	131	20	0.01	9	30	14	<5	<20	24	0.02	<10	80	<10	<1	9
2	G35252	2.0	0.40	35	25	<5	0.61	<1	8	230	1756	4.85	<10	0.30	400	23	<0.01	6	40	18	<5	<20	25	0.03	<10	136	<10	<1	64
3	G35253	2.0	0.43	30	30	<5	1.01	<1	11	254	1501	5.09	<10	0.35	597	63	0.01	9	110	22	<5	<20	46	0.03	<10	149	<10	<1	52
4	G35254	1.9	0.35	25	10	<5	0.28	1	11	226	1569	5.59	<10	0.18	233	27	<0.01	11	100	18	10	<20	4	0.03	<10	119	<10	<1	29
5	G35255	4.0	1.19	45	35	<5	1.07	<1	22	67	8579	4.13	<10	0.58	202	609	0.04	68	320	50	30	<20	57	0.03	<10	45	<10	4	74
6	G35256	2.5	0.27	30	30	<5	0.20	<1	11	230	2020	4.79	<10	0.10	155	44	<0.01	8	130	22	<5	<20	24	0.03	<10	91	<10	<1	14
7	G35257	2.4	0.18	25	25	<5	0.71	<1	12	233	2587	5.33	<10	0.04	145	82	<0.01	7	100	16	<5	<20	90	0.03	<10	84	<10	<1	9
8	G35258	1.8	0.13	25	30	<5	0.22	<1	17	229	1714	4.64	<10	0.01	107	24	<0.01	9	120	16	<5	<20	20	0.02	<10	68	<10	<1	7
9	G35259	2.0	0.13	20	30	<5	0.40	<1	23	227	1601	5.71	<10	0.06	213	20	<0.01	9	140	14	5	<20	17	0.03	<10	30	<10	<1	8
10	G35260	1.4	0.14	10	20	<5	0.34	<1	41	203	1710	7.10	<10	0.07	204	56	<0.01	7	130	14	<5	<20	11	0.04	<10	27	<10	<1	9
11	G35261	1.1	0.25	25	30	<5	0.58	<1	13	225	1170	4.78	<10	0.19	315	32	0.01	8	200	18	5	<20	36	0.03	<10	68	<10	<1	12
12	G35262	1.8	0.19	25	25	<5	0.49	<1	18	215	2642	5.33	<10	0.19	306	51	<0.01	8	60	18	<5	<20	19	0.03	<10	64	<10	<1	12
13	G35263	2.0	0.21	30	25	<5	0.41	<1	11	241	2204	4.68	<10	0.11	235	22	0.01	7	80	18	<5	<20	21	0.03	<10	76	<10	<1	22
14	G35264	2.1	0.22	25	30	<5	0.36	<1	15	200	2640	5.42	<10	0.11	186	22	<0.01	9	40	18	<5	<20	28	0.03	<10	75	<10	<1	30
15	G35265	2.7	0.12	25	30	<5	0.67	<1	10	213	2915	4.41	<10	0.07	346	26	<0.01	9	<10	14	5	<20	41	0.02	<10	54	<10	<1	15
16	G35266	3.5	0.17	35	35	<5	0.27	<1	13	217	4217	4.66	<10	0.10	161	28	<0.01	9	<10	22	<5	<20	35	0.02	<10	65	<10	<1	30
17	G35267	2.1	0.09	30	30	<5	0.25	<1	11	213	2751	4.18	<10	<0.01	92	42	<0.01	8	40	18	<5	<20	34	0.02	<10	63	<10	<1	21
18	G35268	3.3	0.17	40	25	<5	0.33	<1	15	209	2478	6.05	<10	0.04	142	67	<0.01	7	170	22	<5	<20	23	0.03	<10	57	<10	<1	19
19	G35269	2.1	0.21	20	30	<5	0.50	<1	54	241	2565	5.20	<10	0.04	145	61	<0.01	8	160	22	<5	<20	58	0.03	<10	50	<10	<1	21
20	G35270	1.9	0.25	20	35	<5	0.59	<1	16	246	1651	4.95	<10	0.07	272	18	<0.01	10	210	16	<5	<20	45	0.02	<10	69	<10	<1	23
21	G35271	1.1	0.30	20	35	<5	0.58	<1	11	204	1044	4.96	<10	0.13	226	32	0.01	7	390	20	<5	<20	83	0.03	<10	110	<10	<1	26
22	G35272	1.6	0.25	30	35	<5	0.69	<1	9	220	2189	4.24	<10	0.10	272	17	<0.01	7	200	16	<5	<20	82	0.02	<10	81	<10	<1	25
23	G35273	1.9	0.29	25	25	<5	0.67	<1	23	210	1938	5.99	<10	0.13	271	17	<0.01	9	250	16	<5	<20	39	0.03	<10	69	<10	<1	28
24	G35274	1.4	0.35	25	35	<5	0.49	<1	12	198	1964	5.07	<10	0.18	291	18	<0.01	8	310	18	<5	<20	43	0.03	<10	108	<10	<1	41
25	G35275	2.2	0.19	5	30	<5	0.38	<1	20	204	2922	5.66	<10	0.03	148	27	<0.01	9	140	16	<5	<20	26	0.03	<10	82	<10	<1	23

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35276	2.9	0.10	20	30	<5	0.35	<1	15	199	3912	3.96	<10	<0.01	95	29	<0.01	7	100	16	<5	<20	56	<0.01	<10	33	<10	<1	12
27	G35277	1.4	0.35	15	30	<5	0.75	<1	14	182	1447	4.79	<10	0.20	279	20	<0.01	7	290	18	<5	<20	51	0.03	<10	86	<10	<1	30
28	G35278	1.7	0.32	<5	30	<5	0.41	<1	11	203	1763	5.10	<10	0.17	264	51	0.01	6	320	16	<5	<20	33	0.03	<10	122	<10	<1	29
29	G35279	2.5	0.42	10	30	<5	0.54	<1	12	175	1920	6.03	<10	0.26	353	15	<0.01	8	310	18	<5	<20	41	0.04	<10	165	<10	<1	58
30	G35280	2.4	0.29	5	35	<5	0.49	<1	9	227	2671	4.95	<10	0.17	262	16	<0.01	9	210	14	<5	<20	48	0.03	<10	155	<10	<1	36
31	G35281	3.1	0.27	25	25	<5	0.57	<1	13	209	3447	4.13	<10	0.16	243	17	<0.01	7	200	14	<5	<20	42	0.02	<10	95	<10	<1	32
32	G35282	0.9	0.33	15	35	<5	0.52	<1	10	200	906	5.09	<10	0.20	262	16	0.01	7	320	16	<5	<20	42	0.04	<10	160	<10	<1	34
33	G35283	3.2	0.33	10	40	<5	0.53	<1	14	185	3210	5.81	<10	0.18	229	18	0.01	8	350	22	<5	<20	61	0.04	<10	183	<10	<1	39
34	G35284	6.5	0.15	20	30	<5	0.48	<1	14	185	8283	3.96	<10	0.05	209	12	<0.01	8	<10	16	<5	<20	39	0.01	<10	44	<10	<1	30
35	G35285	<0.2	1.09	35	245	<5	0.57	<1	6	89	17	2.12	<10	0.50	491	3	0.08	6	920	18	5	<20	72	0.11	<10	41	<10	2	47
QC DATA:																													
Repeat:																													
1	G35251	2.4	0.10	25	30	<5	0.25	<1	9	217	2099	4.76	<10	<0.01	126	17	<0.01	9	20	12	<5	<20	25	0.02	<10	78	<10	<1	8
10	G35260	1.3	0.12	10	25	<5	0.33	1	41	190	1667	6.82	<10	0.07	198	55	<0.01	9	150	18	<5	<20	14	0.04	<10	28	<10	<1	9
19	G35269	1.9	0.18	10	30	<5	0.49	<1	52	227	2558	5.13	<10	0.04	143	56	<0.01	7	160	20	<5	<20	60	0.02	<10	44	<10	<1	20
Resplit:																													
1	G35251	2.5	0.11	25	25	<5	0.25	<1	10	219	2046	5.18	<10	<0.01	120	20	<0.01	9	30	14	<5	<20	22	0.03	<10	71	<10	<1	10
Standard:																													
Pb113		11.7	0.24	40	50	<5	1.61	34	2	6	2274	1.00	<10	0.10	1543	67	0.01	3	80	5462	35	<20	89	<0.01	<10	7	<10	<1	6939

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/1513S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5589

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

27-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07111
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G37971	0.62	0.018
2	G37972	0.51	0.015
3	G37973	0.53	0.015
4	G37974	0.88	0.026
5	G37975	0.55	0.016
6	G37976	0.54	0.016
7	G37977	0.67	0.020
8	G37978	0.51	0.015
9	G37979	0.46	0.013
10	G37980	0.25	0.007
11	G37981	0.29	0.008
12	G37982	<0.03	<0.001
13	G37983	0.46	0.013
14	G37984	0.44	0.013
15	G37985	0.35	0.010
16	G37986	0.36	0.010
17	G37987	0.41	0.012
18	G37988	0.37	0.011
19	G37989	1.88	0.055
20	G37990	0.40	0.012
21	G37991	0.43	0.013
22	G37992	0.37	0.011
23	G37993	0.56	0.016
24	G37994	0.47	0.014
25	G37995	2.25	0.066
26	G37996	0.39	0.011
27	G37997	0.94	0.027

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5589 27-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G37998	0.53	0.015
29	G37999	0.45	0.013
30	G38000	0.33	0.010
31	E192681	0.09	0.003
32	E192682	0.06	0.002
33	E192683	0.06	0.002
34	E192684	0.25	0.007
35	X09001	0.52	0.015
QC DATA:			
Repeat:			
1	G37971	0.62	0.018
10	G37980	0.25	0.007
25	G37995	2.18	0.064
27	G37997	0.89	0.026
Resplits:			
1	G37971	0.59	0.017
Standard:			
SI25		1.82	0.053

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO-TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5589

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07111
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G37971	1.5	3.17	35	40	5	1.01	1	16	40	881	6.20	<10	1.95	1466	98	0.03	1	3410	136	<5	<20	29	<0.01	<10	65	<10	6	344
2	G37972	1.9	3.59	35	40	15	0.55	6	17	36	1042	8.13	<10	2.40	1719	62	0.03	2	2500	166	<5	<20	24	<0.01	<10	94	<10	5	418
3	G37973	1.8	3.19	30	35	15	0.47	2	17	51	957	7.50	<10	2.21	1538	72	0.02	1	2270	94	<5	<20	17	<0.01	<10	83	<10	4	347
4	G37974	2.3	3.30	35	30	10	0.50	2	19	61	1195	7.95	<10	2.26	1607	62	0.02	1	2430	88	<5	<20	26	<0.01	<10	86	<10	4	363
5	G37975	1.9	3.12	30	35	20	0.43	2	17	58	727	7.39	<10	2.24	1572	62	0.02	1	2060	54	<5	<20	16	<0.01	<10	87	<10	3	306
6	G37976	3.7	2.99	30	35	<5	0.48	1	18	64	924	7.32	<10	2.07	1579	71	0.03	2	1950	34	<5	<20	30	<0.01	<10	85	<10	3	401
7	G37977	4.8	1.62	40	25	<5	1.76	3	23	63	1478	7.38	<10	1.17	797	97	0.03	2	1800	166	<5	<20	165	<0.01	<10	36	<10	2	224
8	G37978	1.7	1.75	30	25	<5	1.25	1	15	72	754	5.10	<10	1.44	843	36	0.03	2	1490	46	<5	<20	141	<0.01	<10	41	<10	3	207
9	G37979	1.7	1.18	30	25	<5	2.43	5	13	65	779	4.13	<10	1.50	2146	46	0.03	4	1240	118	<5	<20	243	<0.01	<10	28	<10	4	229
10	G37980	1.0	1.37	15	25	<5	3.29	1	9	80	534	3.57	<10	1.56	1667	50	0.03	4	1020	44	<5	<20	340	<0.01	<10	39	<10	3	172
11	G37981	0.8	1.51	15	30	<5	3.63	1	8	81	472	3.36	<10	1.44	837	31	0.04	4	1080	36	<5	<20	353	<0.01	<10	54	<10	4	184
12	G37982	<0.2	0.98	10	235	<5	0.63	<1	6	123	4	2.32	<10	0.58	540	<1	0.13	7	800	8	<5	<20	86	0.13	<10	42	<10	5	43
13	G37983	1.4	1.58	15	30	<5	3.31	1	11	80	761	3.83	<10	1.31	837	23	0.05	5	1060	44	<5	<20	351	<0.01	<10	49	<10	4	223
14	G37984	1.6	1.63	20	30	<5	3.12	1	13	79	619	4.83	<10	1.25	1231	23	0.05	5	1070	98	<5	<20	301	<0.01	<10	50	<10	4	234
15	G37985	1.3	1.45	20	30	<5	3.04	2	12	86	617	4.19	<10	1.16	1251	42	0.04	4	1090	64	<5	<20	289	<0.01	<10	44	<10	4	293
16	G37986	1.1	1.28	20	25	<5	3.18	1	10	79	617	3.80	<10	0.99	1078	29	0.04	4	970	60	<5	<20	297	<0.01	<10	37	<10	3	163
17	G37987	1.0	1.29	15	30	<5	3.09	1	9	86	711	3.41	<10	1.00	936	39	0.04	3	990	36	<5	<20	317	<0.01	<10	41	<10	3	172
18	G37988	1.1	1.44	15	30	<5	3.47	1	10	72	652	3.77	<10	1.24	1395	44	0.04	3	1110	58	<5	<20	264	<0.01	<10	48	<10	4	229
19	G37989	3.9	1.08	35	45	<5	1.03	2	18	60	8539	4.37	20	0.56	213	557	0.06	65	320	60	20	<20	63	0.04	<10	38	<10	8	72
20	G37990	1.1	1.36	15	30	<5	2.92	1	9	75	512	3.49	<10	1.18	1124	57	0.04	3	1020	48	<5	<20	255	<0.01	<10	38	<10	3	213
21	G37991	1.2	1.19	15	30	<5	3.39	2	9	82	665	3.50	<10	0.94	938	60	0.03	3	990	70	<5	<20	321	<0.01	<10	32	<10	3	232
22	G37992	0.7	1.40	15	35	<5	3.47	<1	10	79	516	3.50	<10	1.10	1135	35	0.04	3	1010	32	<5	<20	312	<0.01	<10	36	<10	3	240
23	G37993	1.4	0.58	30	25	<5	2.09	4	13	58	737	4.30	<10	0.25	389	42	0.04	3	1230	102	<5	<20	198	<0.01	<10	16	<10	3	199
24	G37994	1.1	1.49	25	30	<5	3.39	1	15	78	673	4.75	<10	1.19	1234	52	0.03	4	1190	40	<5	<20	314	<0.01	<10	38	<10	3	292
25	G37995	0.9	1.30	25	30	<5	3.54	2	11	85	514	3.92	<10	1.15	1348	50	0.04	5	1110	62	<5	<20	294	<0.01	<10	37	<10	3	219

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G37996	1.2	1.23	25	30	<5	2.58	8	12	70	519	3.56	<10	1.03	930	63	0.03	5	1250	110	<5	<20	276	<0.01	<10	35	<10	4	222
27	G37997	2.0	1.01	40	30	<5	3.06	4	15	79	699	4.15	<10	0.84	1070	41	0.04	6	1140	114	<5	<20	269	<0.01	<10	30	<10	4	190
28	G37998	0.9	1.13	20	30	<5	3.87	1	11	80	508	3.93	<10	0.96	970	70	0.04	5	1000	44	<5	<20	398	<0.01	<10	37	<10	4	216
29	G37999	0.6	1.33	15	30	<5	4.68	1	13	63	593	3.86	<10	1.08	1047	51	0.04	4	1110	34	<5	<20	515	<0.01	<10	39	<10	5	190
30	G38000	0.9	1.41	15	30	<5	4.14	2	13	77	628	4.03	<10	1.12	980	51	0.04	5	1070	32	<5	<20	422	<0.01	<10	46	<10	5	166
31	E192681	0.6	1.06	15	40	10	3.21	<1	7	101	28	4.86	<10	1.43	1488	6	0.15	13	540	42	<5	<20	223	0.07	<10	95	<10	4	66
32	E192682	0.5	1.07	10	45	10	3.91	<1	7	108	63	4.60	<10	1.45	1400	8	0.15	13	590	26	<5	<20	271	0.07	<10	103	<10	4	68
33	E192683	0.4	0.96	15	45	5	4.00	<1	8	96	16	3.96	<10	1.28	1414	7	0.07	15	670	16	<5	<20	257	0.06	<10	94	<10	5	59
34	E192684	1.5	0.93	20	45	<5	2.94	<1	12	114	9	3.03	<10	1.11	1132	10	0.08	23	890	18	<5	<20	185	0.08	<10	85	<10	7	52
35	X09001	0.9	1.42	15	35	<5	4.29	1	10	75	489	4.21	<10	1.10	1085	120	0.04	6	1160	34	<5	<20	452	<0.01	<10	51	<10	5	225
QC DATA:																													
Repeat:																													
1	G37971	1.7	2.91	40	35	<5	0.95	2	16	42	847	6.34	<10	1.79	1468	92	0.04	2	3370	138	<5	<20	30	<0.01	<10	67	<10	6	370
10	G37980	1.2	1.34	15	25	<5	3.12	1	10	83	500	3.74	<10	1.52	1768	49	0.03	4	1020	48	<5	<20	350	<0.01	<10	40	<10	3	189
Resplit:																													
1	G37971	1.7	2.86	40	50	<5	1.15	3	19	56	910	7.05	<10	1.72	1526	123	0.03	2	3230	150	<5	<20	40	<0.01	<10	71	<10	5	410
Standard:																													
Pb113		10.9	0.26	60	70	<5	1.81	57	2	2	2176	1.22	<10	0.10	1517	58	0.02	1	90	5440	10	<20	72	0.01	<10	7	<10	1	7131

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5589
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5590

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

27-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07112
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09002	0.32	0.009
2	X09003	0.51	0.015
3	X09004	0.34	0.010
4	X09005	0.53	0.015
5	X09006	0.69	0.020
6	X09007	0.61	0.018
7	X09008	0.70	0.020
8	X09009	0.41	0.012
9	X09010	3.70	0.108
10	X09011	0.48	0.014
11	X09012	0.60	0.017
12	X09013	0.52	0.015
13	X09014	0.55	0.016
14	X09015	0.50	0.015
15	X09016	0.43	0.013
16	X09017	0.90	0.026
17	X09018	0.55	0.016
18	X09019	0.36	0.010
19	X09020	0.44	0.013
20	X09021	0.66	0.019
21	X09022	0.81	0.024
22	X09023	<0.03	<0.001
23	X09024	0.61	0.018
24	X09025	0.40	0.012
25	X09026	0.63	0.018
26	X09027	0.48	0.014

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5590 27-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	X09028	0.65	0.019
28	X09029	0.67	0.020
29	X09030	0.49	0.014
30	X09031	0.46	0.013
31	X09032	0.56	0.016
32	X09033	0.28	0.008
33	X09034	0.40	0.012
34	X09035	0.66	0.019
35	X09036	0.56	0.016
QC DATA:			
Repeat:			
1	X09002	0.33	0.010
9	X09010	3.60	0.105
9	X09010	3.90	0.114
10	X09011	0.46	0.013
19	X09020	0.41	0.012
Resplits:			
1	X09002	0.32	0.009
Standard:			
SI25		1.82	0.053

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5590

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1


No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07112
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09002	0.8	1.27	15	35	<5	3.70	1	11	74	409	3.83	<10	1.00	1152	37	0.04	5	1130	37	<5	<20	569	<0.01	<10	40	<10	4	202
2	X09003	1.0	1.49	15	40	<5	3.49	1	15	74	601	4.23	<10	1.13	1181	59	0.04	6	1230	29	<5	<20	447	<0.01	<10	45	<10	5	216
3	X09004	0.6	1.47	20	40	<5	3.55	<1	11	74	376	3.99	<10	1.21	953	34	0.04	5	1170	22	<5	<20	514	<0.01	<10	48	<10	4	211
4	X09005	1.4	1.10	30	30	<5	3.10	<1	12	72	634	4.03	<10	0.90	768	41	0.03	4	1270	104	<5	<20	401	<0.01	<10	30	<10	4	205
5	X09006	1.5	1.08	15	30	<5	3.80	6	12	70	657	3.56	<10	0.91	1033	97	0.03	4	1120	82	<5	<20	501	<0.01	<10	32	<10	4	370
6	X09007	2.1	0.86	25	30	<5	3.88	18	16	94	893	4.91	<10	0.69	1391	95	0.03	5	1040	395	<5	<20	408	<0.01	<10	27	<10	3	723
7	X09008	9.2	0.69	105	30	<5	3.02	4	12	101	476	4.01	<10	0.52	913	77	0.02	4	1380	93	65	<20	337	<0.01	<10	21	<10	4	355
8	X09009	0.8	1.41	30	40	<5	4.61	1	18	89	481	5.59	<10	1.21	1054	71	0.03	4	1410	26	<5	<20	572	<0.01	<10	66	<10	4	202
9	X09010	2.6	1.35	20	35	5	3.90	2	19	91	483	5.74	<10	1.12	973	127	0.03	4	1670	78	<5	<20	455	<0.01	<10	62	<10	5	219
10	X09011	0.7	1.31	20	40	<5	3.95	1	16	69	441	5.21	<10	1.24	1063	81	0.03	3	1540	27	<5	<20	444	<0.01	<10	64	<10	5	197
11	X09012	0.9	1.27	20	40	<5	4.41	1	17	91	540	4.47	<10	1.07	977	95	0.03	4	1500	38	<5	<20	473	<0.01	<10	55	<10	4	191
12	X09013	0.9	1.45	15	40	<5	4.42	1	18	86	603	4.78	<10	1.19	974	155	0.03	4	1630	34	<5	<20	467	<0.01	<10	67	<10	5	215
13	X09014	0.7	1.38	20	35	<5	3.69	<1	13	79	573	4.24	<10	1.21	973	88	0.03	4	1300	34	<5	<20	460	<0.01	<10	50	<10	5	271
14	X09015	0.6	1.29	15	35	<5	3.99	1	14	72	510	4.12	<10	1.09	1128	90	0.03	4	1230	32	<5	<20	485	<0.01	<10	40	<10	5	280
15	X09016	1.2	0.72	25	25	<5	3.51	4	15	80	517	4.62	<10	0.55	634	79	0.03	3	1440	61	10	<20	431	<0.01	<10	26	<10	4	164
16	X09017	3.2	1.18	20	35	<5	4.10	1	18	69	1115	4.85	<10	0.94	771	96	0.03	4	1690	75	<5	<20	538	<0.01	<10	55	<10	5	241
17	X09018	0.9	1.43	20	35	<5	3.88	1	21	51	756	4.97	<10	1.19	1032	111	0.03	4	1800	26	<5	<20	473	<0.01	<10	78	<10	5	312
18	X09019	0.8	1.17	15	35	<5	4.17	2	19	72	547	4.83	<10	0.96	884	80	0.03	4	1820	66	<5	<20	477	<0.01	<10	59	<10	5	233
19	X09020	0.7	1.27	15	40	<5	4.39	1	16	76	432	4.22	<10	1.08	924	132	0.03	5	1860	32	<5	<20	482	<0.01	<10	70	<10	5	203
20	X09021	2.1	1.30	25	30	<5	4.53	1	18	75	531	4.45	<10	1.16	916	172	0.03	5	1780	51	<5	<20	522	<0.01	<10	61	<10	6	235
21	X09022	1.2	1.31	35	30	<5	4.50	5	19	70	448	4.10	<10	1.20	1306	109	0.03	5	1880	35	5	<20	490	<0.01	<10	55	<10	5	372
22	X09023	0.2	1.03	10	295	<5	0.72	<1	8	91	2	2.14	<10	0.56	619	2	0.10	8	970	11	<5	<20	95	0.18	<10	44	<10	5	50
23	X09024	0.6	1.37	20	35	<5	4.73	1	15	65	423	4.44	<10	1.16	1152	79	0.03	4	1830	35	<5	<20	542	<0.01	<10	67	<10	5	247
24	X09025	0.9	1.22	20	30	<5	4.22	2	19	81	597	5.56	<10	1.05	924	77	0.03	4	1770	51	<5	<20	511	<0.01	<10	58	<10	4	227
25	X09026	1.0	1.28	15	35	<5	3.75	2	18	98	748	4.73	<10	1.10	1038	174	0.03	5	1780	26	<5	<20	535	<0.01	<10	70	<10	5	242

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09027	0.8	1.30	20	35	<5	4.56	2	18	90	440	4.15	<10	1.12	1265	102	0.03	5	1750	26	<5	<20	465	<0.01	<10	59	<10	5	212
27	X09028	0.8	1.52	30	35	<5	4.70	1	20	75	587	4.92	<10	1.29	1151	72	0.03	5	1870	22	<5	<20	505	<0.01	<10	59	<10	5	243
28	X09029	1.2	1.25	25	30	5	3.80	1	22	89	522	5.74	<10	1.00	1102	77	0.03	4	1920	69	<5	<20	349	<0.01	<10	54	<10	5	252
29	X09030	0.7	1.41	20	35	<5	4.55	1	21	84	528	4.73	<10	1.20	1096	109	0.03	6	1880	22	<5	<20	432	<0.01	<10	67	<10	6	245
30	X09031	0.8	1.31	25	35	<5	4.19	1	18	77	456	4.71	<10	1.05	967	124	0.02	4	1870	27	<5	<20	453	<0.01	<10	48	<10	5	222
31	X09032	0.6	1.18	15	35	<5	4.25	1	17	91	500	4.18	<10	0.91	1054	87	0.03	5	1720	26	<5	<20	488	<0.01	<10	54	<10	5	207
32	X09033	3.0	1.17	40	50	<5	1.14	4	24	55	2591	3.60	20	0.61	223	236	0.04	14	660	72	10	<20	71	0.06	<10	44	<10	9	289
33	X09034	0.8	1.26	30	30	<5	3.82	1	17	83	532	4.89	<10	1.03	961	109	0.02	4	1950	34	<5	<20	430	<0.01	<10	54	<10	5	207
34	X09035	0.7	1.46	20	30	<5	3.53	1	18	74	559	5.71	<10	1.23	943	118	0.03	4	1860	38	<5	<20	402	<0.01	<10	64	<10	5	225
35	X09036	<0.2	1.42	20	40	<5	5.13	2	24	92	843	6.25	<10	1.15	1495	168	0.03	5	1970	27	<5	<20	482	<0.01	<10	63	<10	6	184
QC DATA:																													
Repeat:																													
1	X09002	0.8	1.15	15	30	<5	3.86	1	11	69	386	3.83	<10	0.97	1116	31	0.03	5	1070	32	<5	<20	545	<0.01	<10	40	<10	4	196
10	X09011	0.7	1.48	20	40	<5	4.58	2	18	78	444	5.27	<10	1.24	1181	88	0.03	4	1720	30	<5	<20	478	<0.01	<10	65	<10	5	217
19	X09020	0.6	1.27	20	35	<5	4.46	1	16	79	414	4.25	<10	1.06	990	119	0.03	5	1970	34	<5	<20	533	<0.01	<10	69	<10	5	222
Resplit:																													
1	X09002	0.8	1.34	15	35	<5	4.60	2	12	94	399	4.15	<10	1.06	1206	39	0.03	5	1120	40	<5	<20	526	<0.01	<10	42	<10	5	256
Standard:																													
Pb113		11.4	0.28	70	80	<5	1.78	71	2	<1	2176	1.40	<10	0.11	2237	67	0.02	1	220	5610	10	<20	179	0.02	<10	7	<10	1	7011

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish



ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5589
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5592

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

15-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07113
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	X09037	0.41	0.012		
2	X09038	0.77	0.022		
3	X09039	0.91	0.027	42.3	1.234
4	X09040	0.26	0.008		
5	X09041	0.28	0.008		
6	X09042	0.72	0.021		
7	X09043	0.71	0.021		
8	X09044	0.71	0.021		
9	X09045	0.51	0.015		
10	X09046	0.49	0.014		
11	X09047	0.47	0.014		
12	X09048	0.42	0.012		
13	X09049	0.45	0.013		
14	X09050	0.70	0.020		
15	X09051	0.66	0.019		
16	X09052	0.68	0.020		
17	X09053	<0.03	<0.001		
18	X09054	0.52	0.015		
19	X09055	0.42	0.012		
20	X09056	0.52	0.015		
21	X09057	0.56	0.016		
22	X09058	0.62	0.018		
23	X09059	0.40	0.012		
24	X09060	0.51	0.015		
25	X09061	0.48	0.014		
26	X09062	0.42	0.012		
27	X09063	1.03	0.030		
28	X09064	0.34	0.010		
29	X09065	0.45	0.013		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5592

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
30	X09066	0.08	0.002		
31	X09067	0.43	0.013		
32	X09068	0.50	0.015		
33	X09069	0.19	0.006		
34	X09070	0.31	0.009		
35	X09071	0.39	0.011		
QC DATA:					
Repeat:					
1	X09037	0.41	0.012		
3	X09039			41.3	1.204
10	X09046	0.52	0.015		
19	X09055	0.39	0.011		
Resplits:					
1	X09037	0.41	0.012		
Standard:					
SI25		1.81	0.053		
Pb113				22.7	0.662

AU: 30g FA/AA-Finish

per Bruce Ipes

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

18-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5592

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07113
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09037	0.6	1.35	25	55	<5	4.36	<1	11	81	540	3.78	<10	1.02	772	129	0.02	4	1800	28	<5	<20	390	<0.01	<10	51	<10	6	109
2	X09038	1.5	1.57	20	50	<5	4.75	<1	18	64	867	4.69	<10	1.10	793	147	0.02	4	1780	20	<5	<20	432	<0.01	<10	56	<10	5	140
3	X09039	>30	0.96	50	35	<5	3.60	3	21	80	1394	4.69	<10	0.71	633	60	0.02	5	1380	44	95	<20	380	<0.01	<10	33	<10	4	145
4	X09040	2.6	1.33	15	45	<5	3.73	<1	14	66	436	3.66	<10	1.08	750	93	0.02	4	1670	30	<5	<20	388	<0.01	<10	47	<10	5	158
5	X09041	1.2	1.41	20	50	<5	4.57	<1	13	67	394	4.05	<10	1.22	1176	71	0.02	3	1650	22	<5	<20	452	<0.01	<10	56	<10	5	144
6	X09042	1.5	1.58	20	50	<5	3.62	<1	14	59	783	4.33	<10	1.39	795	130	0.02	3	1520	16	<5	<20	396	<0.01	<10	57	<10	5	158
7	X09043	3.4	0.87	25	35	<5	3.88	1	19	85	1108	5.51	<10	0.78	1143	65	0.02	3	1230	56	5	<20	270	<0.01	<10	29	<10	4	87
8	X09044	1.3	1.49	20	40	<5	3.82	<1	13	95	816	4.09	<10	1.27	681	84	0.02	3	1300	20	<5	<20	420	<0.01	<10	39	<10	4	158
9	X09045	1.9	1.28	20	40	<5	4.15	1	15	78	819	4.56	<10	1.10	1066	58	0.02	3	1520	52	<5	<20	342	<0.01	<10	40	<10	5	169
10	X09046	2.5	1.37	25	45	<5	5.18	1	14	79	814	4.26	<10	1.29	1434	86	0.02	3	1560	38	<5	<20	460	<0.01	<10	40	<10	4	217
11	X09047	2.2	0.81	20	40	<5	4.38	1	11	85	571	3.37	<10	0.82	1155	64	0.01	3	1580	30	5	<20	355	<0.01	<10	24	<10	4	159
12	X09048	1.8	0.51	15	35	<5	4.08	1	13	110	925	3.44	<10	0.65	1529	146	0.01	3	1350	54	<5	<20	273	<0.01	<10	15	<10	4	92
13	X09049	1.5	0.87	20	40	<5	5.25	<1	12	92	608	3.39	<10	0.60	973	81	0.01	3	1470	24	<5	<20	464	<0.01	<10	20	<10	4	120
14	X09050	1.3	1.20	25	40	<5	5.33	1	14	101	1086	3.98	<10	0.86	1155	62	0.01	3	1560	26	<5	<20	437	<0.01	<10	24	<10	4	199
15	X09051	1.2	1.54	15	45	<5	5.83	1	12	103	917	3.97	<10	1.02	1087	150	0.02	3	1380	32	<5	<20	490	<0.01	<10	34	<10	4	195
16	X09052	0.9	1.36	15	45	<5	5.12	<1	13	103	906	3.77	<10	0.72	687	170	0.01	3	1420	20	<5	<20	492	<0.01	<10	28	<10	4	109
17	X09053	<0.2	1.05	10	210	<5	0.63	<1	8	93	3	2.13	<10	0.54	727	<1	0.06	7	980	12	<5	<20	91	0.16	<10	43	<10	5	51
18	X09054	1.1	0.88	10	35	<5	4.47	<1	13	111	874	3.66	<10	0.51	646	135	0.01	3	1440	26	<5	<20	389	<0.01	<10	18	<10	4	73
19	X09055	0.8	0.91	10	55	<5	5.46	<1	11	79	492	2.81	<10	0.75	1170	94	0.01	3	1540	14	<5	<20	408	<0.01	<10	19	<10	4	106
20	X09056	1.3	0.50	10	45	<5	5.92	1	14	112	954	4.31	<10	0.49	1073	102	0.01	2	1300	50	<5	<20	440	<0.01	<10	11	<10	3	59
21	X09057	2.3	0.43	15	35	<5	4.71	<1	14	98	925	4.46	<10	0.53	1165	65	<0.01	3	1590	28	<5	<20	282	<0.01	<10	12	<10	5	46
22	X09058	7.2	0.42	25	35	<5	4.98	2	19	129	982	4.54	<10	0.40	1087	125	<0.01	3	1640	54	10	<20	299	<0.01	<10	8	<10	4	53
23	X09059	1.3	0.72	10	35	<5	5.83	1	14	101	810	3.92	<10	0.59	770	129	0.01	3	1650	44	<5	<20	461	<0.01	<10	14	<10	4	89
24	X09060	1.2	1.02	10	40	<5	5.86	<1	14	94	937	3.79	<10	0.72	877	106	<0.01	3	1550	64	<5	<20	488	<0.01	<10	19	<10	4	128
25	X09061	0.9	1.02	10	45	<5	6.86	<1	14	92	778	3.49	<10	0.64	965	56	<0.01	3	1520	76	<5	<20	540	<0.01	<10	18	<10	4	101

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09062	1.2	0.77	10	35	<5	3.98	<1	18	107	635	4.08	<10	0.36	430	188	0.01	3	1930	126	<5	<20	309	<0.01	<10	16	<10	4	66
27	X09063	3.7	1.12	75	80	<5	0.78	5	19	67	3317	3.95	20	0.44	319	229	0.02	20	400	160	35	<20	45	0.04	<10	42	<10	6	146
28	X09064	2.3	0.38	10	35	<5	4.94	2	19	96	902	4.95	<10	0.36	608	138	0.01	3	1520	160	<5	<20	468	<0.01	<10	13	<10	3	41
29	X09065	3.5	0.42	15	30	<5	3.98	2	19	124	600	4.48	<10	0.38	591	202	<0.01	3	1700	84	10	<20	319	<0.01	<10	12	<10	3	65
30	X09066	0.8	0.22	<5	50	5	>10	<1	5	167	78	2.05	<10	0.75	1957	39	<0.01	4	400	74	<5	<20	1047	<0.01	<10	3	<10	3	33
31	X09067	1.6	0.89	10	35	<5	4.78	<1	14	88	785	4.30	<10	0.85	821	185	0.01	2	1540	48	<5	<20	413	<0.01	<10	23	<10	3	85
32	X09068	1.1	0.89	10	45	<5	6.25	<1	12	95	612	3.44	<10	0.62	748	116	0.01	3	1560	38	<5	<20	599	<0.01	<10	28	<10	4	116
33	X09069	0.8	0.90	10	40	<5	6.69	<1	13	88	429	3.30	<10	0.70	1079	82	<0.01	2	1660	46	<5	<20	485	<0.01	<10	22	<10	4	126
34	X09070	0.8	0.99	10	45	<5	6.54	<1	13	107	498	3.99	<10	0.78	1090	111	0.01	3	1530	36	<5	<20	515	<0.01	<10	27	<10	4	174
35	X09071	1.0	0.71	10	40	<5	5.28	<1	13	106	558	3.97	<10	0.51	793	100	0.01	3	1750	26	<5	<20	384	<0.01	<10	19	<10	4	106
QC DATA:																													
Repeat:																													
1	X09037	0.8	1.27	20	55	<5	4.55	<1	12	85	511	4.02	<10	0.95	844	127	0.02	4	1780	30	<5	<20	393	<0.01	<10	52	<10	6	114
10	X09046	2.3	1.43	25	45	<5	5.39	1	14	77	801	4.35	<10	1.30	1469	82	0.01	3	1590	40	<5	<20	447	<0.01	<10	40	<10	4	225
19	X09055	0.9	0.82	10	45	<5	6.01	1	11	83	469	2.98	<10	0.75	1278	97	0.01	3	1590	14	<5	<20	454	<0.01	<10	22	<10	4	110
Resplit:																													
1	X09037	0.8	1.38	25	55	<5	4.40	1	12	79	493	4.06	<10	0.92	841	127	0.01	4	1840	30	<5	<20	407	<0.01	<10	51	<10	6	112
Standard:																													
Pb113		11.2	0.26	40	70	<5	1.77	46	3	1	2235	1.04	<10	0.09	1548	73	<0.01	1	90	5480	10	<20	89	0.01	<10	7	<10	1	7112

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/n5592S
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5593

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

11-Sep-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 070114
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35286	0.47	0.014
2	G35287	1.30	0.038
3	G35288	0.65	0.019
4	G35289	0.81	0.024
5	G35290	0.74	0.022
6	G35291	0.41	0.012
7	G35292	0.18	0.005
8	G35293	0.50	0.015
9	G35294	0.31	0.009
10	G35295	0.14	0.004
11	G35296	0.08	0.002
12	G35297	0.16	0.005
13	G35298	0.16	0.005
14	G35299	0.83	0.024
15	G35300	0.66	0.019
16	G35503	0.54	0.016
17	G35504	0.83	0.024
18	G35505	0.58	0.017
19	G35506	0.52	0.015
20	G35507	0.81	0.024
21	G35508	0.34	0.010
22	G35509	0.23	0.007
23	G35510	0.44	0.013
24	G35511	1.41	0.041
25	G35512	0.30	0.009
26	G35513	1.50	0.044

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS-5593 11-Sep-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	G35514	1.82	0.053
28	G35515	1.62	0.047
29	G35516	2.43	0.071
30	G35517	1.61	0.047
31	G35518	1.59	0.046
32	G35519	<0.03	<0.001
33	G35520	1.62	0.047
34	G35521	1.97	0.057
35	G35522	2.08	0.061

QC DATA:

Repeat:

1	G35286	0.44	0.013
10	G35295	0.16	0.005
19	G35506	0.52	0.015

Resplits:

1	G35286	0.40	0.012

Standard:

S125		1.81	0.053

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
XLS/07

11-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5593

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 070114
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35286	2.7	0.23	<5	30	<5	0.83	1	15	184	2248	5.18	<10	0.21	361	39	0.01	2	280	12	<5	<20	33	<0.01	<10	65	<10	<1	18
2	G35287	3.0	0.34	10	35	<5	0.70	1	10	162	2852	4.56	<10	0.22	322	15	0.01	2	460	10	<5	<20	48	<0.01	<10	71	<10	1	28
3	G35288	3.1	0.41	5	30	<5	0.87	1	12	158	3085	4.69	<10	0.41	541	18	0.01	2	460	14	<5	<20	52	<0.01	<10	47	<10	1	31
4	G35289	3.3	0.40	10	30	<5	0.87	2	9	155	3058	5.37	<10	0.37	513	10	0.01	2	450	12	<5	<20	51	<0.01	<10	53	<10	1	55
5	G35290	5.2	0.41	10	30	<5	0.98	1	9	156	5537	4.44	<10	0.38	606	12	0.01	2	370	10	<5	<20	51	<0.01	<10	43	<10	1	41
6	G35291	3.1	0.57	20	35	<5	3.68	2	10	121	1726	5.13	<10	1.08	2075	9	0.01	1	520	16	<5	<20	122	<0.01	<10	56	<10	3	57
7	G35292	1.1	0.97	20	105	<5	2.05	1	7	107	575	4.77	<10	0.82	1208	8	0.01	1	940	10	<5	<20	110	<0.01	<10	28	<10	5	69
8	G35293	1.8	0.81	30	30	<5	0.86	1	17	112	1042	4.91	<10	0.66	618	12	0.01	1	670	12	<5	<20	29	<0.01	<10	28	<10	3	41
9	G35294	1.2	0.81	20	80	<5	1.37	1	8	95	827	4.88	<10	0.69	689	8	0.01	<1	880	10	<5	<20	92	<0.01	<10	36	<10	4	41
10	G35295	0.7	0.76	15	50	<5	2.48	<1	11	82	607	3.61	<10	0.59	751	8	0.01	2	1000	10	<5	<20	183	0.02	<10	19	<10	5	42
11	G35296	0.5	0.58	10	60	<5	4.04	1	7	79	292	3.39	<10	0.44	1053	8	0.01	2	1080	10	<5	<20	263	0.03	<10	26	<10	6	39
12	G35297	0.8	0.72	10	50	<5	2.86	<1	9	74	411	3.34	<10	0.53	727	7	0.01	2	1130	10	<5	<20	212	0.03	<10	22	<10	6	33
13	G35298	1.0	0.81	25	50	<5	2.09	<1	8	97	509	3.62	<10	0.68	721	10	0.01	2	1020	10	<5	<20	157	<0.01	<10	20	<10	5	38
14	G35299	1.7	0.86	35	30	<5	1.75	1	25	121	974	6.16	<10	0.68	908	11	0.02	1	840	14	<5	<20	47	<0.01	<10	21	<10	4	30
15	G35300	1.1	1.03	50	50	<5	1.88	1	8	95	693	4.29	<10	0.90	1065	9	0.01	<1	890	12	<5	<20	46	<0.01	<10	21	<10	4	45
16	G35503	1.0	0.94	50	35	5	1.98	1	9	113	558	4.26	<10	0.84	1008	9	0.01	2	840	12	<5	<20	95	<0.01	<10	23	<10	4	52
17	G35504	3.5	0.63	65	30	<5	2.00	1	8	137	1463	4.53	<10	0.47	846	11	0.01	1	800	12	<5	<20	106	<0.01	<10	16	<10	4	42
18	G35505	2.8	0.60	35	30	15	2.82	2	10	101	657	6.84	<10	0.41	1259	11	0.02	<1	770	18	<5	<20	73	<0.01	<10	23	<10	6	34
19	G35506	1.7	1.09	35	35	15	1.19	1	11	138	562	5.77	<10	0.83	904	12	0.01	<1	690	14	<5	<20	38	<0.01	<10	34	<10	3	76
20	G35507	3.1	0.88	50	35	5	1.53	2	10	116	1290	7.38	<10	0.66	897	9	0.01	<1	700	18	<5	<20	48	<0.01	<10	34	<10	3	38
21	G35508	1.3	0.70	15	65	<5	1.72	<1	7	103	520	3.93	<10	0.49	786	11	0.01	1	890	8	<5	<20	83	<0.01	<10	22	<10	3	38
22	G35509	1.0	0.77	20	60	10	1.82	<1	7	125	319	4.20	<10	0.53	830	7	0.01	2	810	10	<5	<20	78	<0.01	<10	26	<10	3	39
23	G35510	2.5	0.51	10	40	<5	2.09	2	9	134	1293	4.85	<10	0.34	902	12	0.01	1	640	18	<5	<20	140	<0.01	<10	25	<10	3	62
24	G35511	5.6	0.79	95	35	<5	1.70	2	11	126	2567	6.61	<10	0.65	1129	8	0.01	<1	520	24	<5	<20	45	<0.01	<10	34	<10	2	52
25	G35512	3.2	1.12	35	55	<5	1.11	3	20	56	2619	3.60	20	0.61	218	194	0.03	13	650	56	10	<20	65	0.05	<10	38	<10	9	262

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35513	6.3	0.32	70	40	<5	0.97	1	7	176	4241	5.51	<10	0.19	456	8	0.01	1	200	12	<5	<20	38	<0.01	<10	46	<10	<1	19
27	G35514	8.4	0.16	45	35	<5	0.46	1	7	201	6006	4.80	<10	0.09	242	4	0.01	3	100	10	<5	<20	37	<0.01	<10	41	<10	<1	13
28	G35515	7.8	0.26	70	30	<5	0.34	1	9	192	5861	5.43	<10	0.18	230	7	0.01	2	160	12	<5	<20	10	<0.01	<10	54	<10	<1	18
29	G35516	7.4	0.23	25	35	<5	0.21	1	8	195	5659	4.78	<10	0.15	163	5	0.01	3	160	10	<5	<20	50	<0.01	<10	45	<10	<1	17
30	G35517	5.2	0.33	10	30	<5	0.27	1	12	205	4222	6.36	<10	0.20	247	19	0.01	2	220	12	<5	<20	16	<0.01	<10	79	<10	<1	24
31	G35518	5.7	0.44	25	35	<5	0.91	1	9	186	4954	6.10	<10	0.34	226	16	0.01	2	200	14	<5	<20	94	<0.01	<10	104	<10	<1	30
32	G35519	<0.2	0.98	5	240	<5	0.53	<1	7	90	5	2.09	<10	0.57	588	1	0.08	6	980	8	<5	<20	82	0.14	<10	38	<10	4	45
33	G35520	4.9	0.31	15	30	<5	0.24	1	10	187	4266	5.07	<10	0.22	224	17	0.01	2	160	10	<5	<20	11	<0.01	<10	99	<10	<1	24
34	G35521	6.0	0.39	15	35	<5	0.25	1	8	195	4933	5.19	<10	0.26	380	7	0.01	2	160	12	<5	<20	20	<0.01	<10	90	<10	<1	27
35	G35522	5.3	0.29	15	30	<5	0.18	1	6	176	4303	6.81	<10	0.18	224	10	0.01	<1	170	12	<5	<20	23	<0.01	<10	79	<10	<1	29
QC DATA:																													
Repeat:																													
1	G35286	2.5	0.23	<5	30	<5	0.86	1	15	185	2253	5.30	<10	0.21	365	41	0.01	2	280	12	<5	<20	35	<0.01	<10	68	<10	<1	18
10	G35295	0.9	0.72	15	50	<5	2.42	<1	11	85	581	3.63	<10	0.57	768	8	0.01	2	1020	10	<5	<20	188	0.02	<10	19	<10	5	43
19	G35506	1.7	1.09	35	35	10	1.20	1	11	138	550	5.73	<10	0.82	908	12	0.01	<1	680	14	<5	<20	38	<0.01	<10	34	<10	3	77
Resplit:																													
1	G35286	2.5	0.21	<5	30	<5	0.74	1	15	184	2179	5.14	<10	0.19	360	36	0.01	2	240	10	<5	<20	36	<0.01	<10	63	<10	<1	18
Standard:																													
Pb113		11.8	0.24	45	65	<5	1.69	40	2	<1	2240	1.08	<10	0.10	1551	64	0.01	<1	90	5580	5	<20	82	0.01	<10	6	<10	1	6978

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/kk
df/N5593
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5594

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

9-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07115
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09072	0.52	0.015
2	X09073	0.31	0.009
3	X09074	0.41	0.012
4	X09075	0.52	0.015
5	X09076	0.50	0.015
6	X09077	0.57	0.017
7	X09078	0.58	0.017
8	X09079	0.69	0.020
9	X09080	0.60	0.017
10	X09081	0.52	0.015
11	X09082	0.69	0.020
12	X09083	0.76	0.022
13	X09084	0.76	0.022
14	X09085	0.41	0.012
15	X09086	0.33	0.010
16	X09087	1.90	0.055
17	X09088	0.62	0.018
18	X09089	0.67	0.020
19	X09090	0.77	0.022
20	X09091	0.95	0.028
21	X09092	0.72	0.021
22	X09093	0.66	0.019
23	X09094	0.43	0.013
24	X09095	0.53	0.015
25	X09096	0.28	0.008

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5594 9-Oct-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X09097	<0.03	<0.001
27	X09098	0.21	0.006
28	X09099	0.37	0.011
29	X09100	1.11	0.032
30	X09101	0.27	0.008
31	X09102	0.28	0.008
32	X09103	0.39	0.011
33	X09104	0.60	0.017
34	X09105	0.76	0.022
35	X09106	0.79	0.023

QC DATA:

Repeat:

1	X09072	0.48	0.014
10	X09081	0.49	0.014
19	X09090	0.77	0.022
29	X09100	1.01	0.029

Resplits:

1	X09072	0.47	0.014

Standard:

OXI54		1.85	0.054

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
XLS/07

3-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5594

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07115
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09072	1.6	0.51	<5	20	<5	2.88	6	11	81	952	2.88	<10	0.59	524	84	0.02	6	970	92	10	<20	286	0.01	<10	17	<10	<1	235
2	X09073	0.8	0.72	<5	20	<5	3.32	<1	12	56	706	2.76	<10	0.82	705	84	0.02	4	1100	34	<5	<20	262	0.02	<10	25	<10	2	83
3	X09074	1.0	1.29	<5	30	<5	2.94	2	14	57	881	3.59	<10	1.33	673	69	0.02	7	1060	34	25	<20	284	0.03	<10	38	<10	1	138
4	X09075	1.3	0.65	<5	25	<5	2.60	3	13	66	1458	3.27	<10	0.74	631	112	0.02	6	840	44	5	<20	233	0.01	<10	20	<10	<1	93
5	X09076	1.1	1.29	10	30	<5	2.98	<1	10	62	804	2.98	<10	1.12	696	75	0.03	3	910	32	10	<20	302	0.02	<10	36	<10	<1	137
6	X09077	1.2	1.06	10	25	<5	2.63	1	13	69	1099	3.38	<10	0.80	587	133	0.02	5	850	42	10	<20	290	0.02	<10	29	<10	<1	130
7	X09078	1.0	1.03	<5	20	<5	3.00	<1	11	68	894	3.20	<10	0.65	575	84	0.02	4	860	32	5	<20	342	0.02	<10	30	<10	<1	129
8	X09079	1.2	1.08	10	30	<5	3.09	<1	13	69	1045	3.46	<10	0.68	542	122	0.02	4	860	32	5	<20	360	0.02	<10	33	<10	<1	146
9	X09080	1.3	1.02	<5	25	<5	3.12	2	12	78	1116	3.48	<10	0.87	896	114	0.02	7	890	48	10	<20	356	0.02	<10	31	<10	<1	170
10	X09081	1.2	1.01	<5	25	<5	3.36	<1	11	57	990	2.65	<10	0.77	533	89	0.03	2	810	44	<5	<20	432	0.02	<10	33	<10	1	129
11	X09082	0.9	1.33	<5	30	<5	3.09	1	11	59	1280	3.40	<10	1.03	522	130	0.03	8	790	32	25	<20	401	0.02	<10	41	<10	<1	250
12	X09083	4.2	0.49	<5	20	<5	3.43	6	14	80	1606	3.72	<10	0.63	625	115	0.02	7	600	144	<5	<20	407	0.02	<10	15	<10	<1	218
13	X09084	1.1	0.74	15	20	<5	3.06	2	13	73	1186	3.34	<10	0.92	743	116	0.02	5	820	44	<5	<20	284	0.02	<10	18	<10	<1	208
14	X09085	0.8	1.03	5	25	<5	2.74	<1	11	75	730	3.27	<10	1.21	1054	123	0.02	5	930	38	15	<20	222	0.03	<10	27	<10	<1	219
15	X09086	1.1	0.71	<5	15	<5	3.48	2	11	86	748	3.82	<10	0.81	857	129	0.02	6	820	76	10	<20	358	0.08	<10	20	<10	<1	136
16	X09087	3.9	1.05	40	50	<5	0.98	2	21	56	8572	3.97	10	0.63	191	556	0.04	60	90	68	25	<20	51	<0.01	<10	40	<10	8	82
17	X09088	0.9	1.05	25	20	<5	3.01	<1	11	44	925	2.85	<10	1.01	928	78	0.02	4	860	54	10	<20	311	0.02	<10	30	<10	<1	159
18	X09089	1.1	1.46	20	15	<5	3.41	1	11	44	1035	3.23	<10	1.28	802	99	0.02	6	880	50	20	<20	364	0.02	<10	34	<10	<1	269
19	X09090	2.7	0.81	15	20	<5	3.20	1	15	51	1130	3.65	<10	0.72	662	132	0.02	6	1080	64	5	<20	317	0.02	<10	30	<10	<1	154
20	X09091	2.1	1.24	10	25	<5	3.46	2	16	46	1653	4.42	<10	0.77	524	189	0.02	7	1010	60	5	<20	380	0.02	<10	40	<10	<1	164
21	X09092	1.8	1.36	20	35	<5	3.60	2	16	89	1307	4.27	<10	1.28	738	161	0.02	9	920	64	25	<20	356	0.02	<10	37	<10	<1	230
22	X09093	1.6	0.64	15	30	<5	4.03	2	13	119	1088	3.54	<10	0.89	1170	72	0.02	13	700	40	30	<20	351	0.02	<10	14	<10	<1	155
23	X09094	4.2	0.18	60	5	<5	2.91	1	10	140	1188	3.05	<10	0.45	531	73	0.02	11	230	88	45	<20	237	0.01	<10	4	<10	<1	156
24	X09095	3.3	0.27	30	15	<5	2.17	5	13	122	1276	3.70	<10	0.53	500	93	0.02	15	300	206	20	<20	164	0.02	<10	6	<10	<1	368
25	X09096	3.5	0.27	40	20	<5	1.19	1	13	118	1874	3.47	<10	0.51	497	179	0.02	13	230	34	30	<20	43	0.05	<10	4	<10	<1	41

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09097	<0.2	0.86	15	230	20	0.57	<1	6	91	8	2.08	<10	0.50	503	4	0.10	7	770	22	10	<20	58	0.09	<10	42	<10	3	51
27	X09098	5.0	0.28	55	30	<5	1.37	<1	8	112	1437	2.17	<10	0.67	679	154	0.02	8	240	32	50	<20	42	0.01	<10	4	<10	<1	47
28	X09099	1.0	0.35	25	20	<5	1.14	<1	12	115	1595	3.44	<10	0.57	485	156	0.02	12	370	24	15	<20	28	0.01	<10	6	<10	<1	42
29	X09100	0.8	0.51	<5	30	<5	1.73	1	15	78	1297	4.45	<10	1.04	888	197	0.03	20	500	28	15	<20	36	0.03	<10	10	<10	<1	54
30	X09101	1.1	0.24	70	25	<5	0.64	<1	15	124	1369	4.10	<10	0.21	321	113	0.03	18	300	64	5	<20	14	0.01	<10	4	<10	<1	42
31	X09102	0.8	0.37	110	25	<5	1.49	<1	9	132	1331	3.47	<10	0.38	292	167	0.03	9	560	38	15	<20	126	0.02	<10	5	<10	<1	74
32	X09103	0.9	0.30	60	25	<5	1.50	1	12	131	1296	3.37	<10	0.33	282	171	0.03	13	430	54	10	<20	123	0.01	<10	4	<10	<1	82
33	X09104	0.6	0.36	15	25	<5	2.14	1	10	108	1010	3.25	<10	0.58	538	137	0.03	11	770	42	10	<20	136	0.01	<10	7	<10	<1	68
34	X09105	1.1	0.29	5	25	<5	2.07	1	15	145	1366	5.18	<10	0.35	455	74	0.02	9	1100	56	<5	<20	132	0.02	<10	5	<10	<1	46
35	X09106	1.5	0.40	15	25	<5	2.37	2	17	103	1396	4.77	<10	0.51	351	108	0.03	10	1050	62	10	<20	190	0.02	<10	7	<10	<1	157
QC DATA:																													
Repeat:																													
1	X09072	1.7	0.54	<5	15	<5	2.87	5	11	84	905	2.94	<10	0.58	523	91	0.02	6	1010	92	5	<20	261	0.01	<10	19	<10	<1	249
10	X09081	1.2	0.96	15	25	<5	3.30	<1	12	58	916	2.66	<10	0.72	524	96	0.03	4	880	42	5	<20	345	0.02	<10	32	<10	1	140
19	X09090	2.7	0.84	20	25	<5	3.52	2	15	54	1145	3.71	<10	0.73	674	138	0.02	8	1100	66	5	<20	316	0.02	<10	31	<10	<1	159
Resplit:																													
1	X09072	1.5	0.50	5	20	3	2.58	5	12	86	800	3.04	<10	0.54	555	84	0.02	7	1030	84	5	<20	291	0.03	<10	18	<10	1	234
Standard:																													
Pb113		11.4	0.23	40	60	<5	1.68	35	2	5	2166	1.05	<10	0.10	1594	62	0.02	4	80	5564	25	<20	86	<0.01	<10	7	<10	<1	7044

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
dl/5594
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5595

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

9-Oct-07

No. of samples received: 27
Sample Type: Core
Project: KSM
Shipment #: 07116
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35476	0.08	0.002
2	G35477	0.06	0.002
3	G35478	0.11	0.003
4	G35479	0.12	0.003
5	G35480	0.09	0.003
6	G35481	0.18	0.005
7	G35482	0.21	0.006
8	G35483	0.03	0.001
9	G35484	0.04	0.001
10	G35485	1.82	0.053
11	G35486	0.16	0.005
12	G35487	0.06	0.002
13	G35488	0.17	0.005
14	G35489	0.14	0.004
15	G35490	0.12	0.003
16	G35491	0.11	0.003
17	G35492	<0.03	<0.001
18	G35493	0.11	0.003
19	G35494	0.23	0.007
20	G35495	0.10	0.003
21	G35496	0.18	0.005
22	G35497	0.09	0.003
23	G35498	0.07	0.002
24	G35499	0.08	0.002
25	G35500	0.08	0.002
26	G35501	0.36	0.010
27	G35502	0.13	0.004

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5595 9-Oct-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
QC DATA:			
Repeat:			
1	G35476	0.08	0.002
11	G35486	0.12	0.003
19	G35494	0.25	0.007
Resplits:			
1	G35476	0.08	0.002
27	G35502	0.12	0.003
Standard:			
SI235		1.81	0.053

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
XLS/07

15-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5595

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 27
Sample Type: Core
Project: KSM
Shipment #: 07116
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35476	1.9	1.91	35	50	<5	5.39	1	20	62	405	5.38	<10	2.29	2511	14	0.03	23	1450	186	30	<20	271	0.15	<10	81	<10	4	128
2	G35477	1.2	0.89	45	45	<5	3.85	4	16	68	168	3.23	<10	0.90	1533	30	0.03	19	1180	174	10	<20	181	0.13	<10	51	<10	1	263
3	G35478	1.5	1.48	40	65	<5	3.59	2	22	71	571	4.66	<10	1.76	1986	13	0.03	24	2050	176	15	<20	190	0.14	<10	109	<10	5	211
4	G35479	1.6	1.36	45	65	<5	3.07	4	19	84	404	4.06	<10	1.55	1605	9	0.04	31	1950	200	15	<20	149	0.14	<10	115	<10	5	257
5	G35480	2.6	0.92	50	45	<5	3.19	9	15	91	404	3.29	<10	1.07	1607	12	0.04	18	850	520	15	<20	124	0.10	<10	70	<10	2	608
6	G35481	3.7	1.25	30	50	<5	3.15	16	22	51	664	4.60	<10	1.34	2186	14	0.02	19	1320	472	15	<20	119	0.11	<10	53	<10	3	1046
7	G35482	5.7	1.02	30	45	<5	2.49	65	15	44	1051	5.04	<10	0.97	1739	24	0.02	10	1170	632	15	<20	105	0.08	<10	32	<10	<1	4172
8	G35483	1.0	0.71	45	75	<5	1.95	5	8	38	76	1.64	<10	0.50	830	5	0.04	4	1120	194	20	<20	113	0.04	<10	27	<10	2	282
9	G35484	0.7	0.74	45	100	20	2.09	<1	7	50	65	1.74	<10	0.56	785	4	0.06	3	1180	46	10	<20	139	0.06	<10	38	<10	4	54
10	G35485	3.9	1.11	60	50	<5	1.16	<1	24	61	8577	4.34	<10	0.61	217	651	0.04	66	600	76	15	<20	60	0.09	<10	45	<10	5	81
11	G35486	1.2	0.68	45	40	<5	1.94	1	15	40	205	2.83	<10	0.51	723	10	0.05	8	1130	196	20	<20	119	0.04	<10	35	<10	<1	75
12	G35487	0.5	0.67	50	65	<5	2.25	<1	11	46	118	1.86	<10	0.48	731	4	0.05	3	1130	58	5	<20	117	0.05	<10	38	<10	3	50
13	G35488	2.1	1.17	50	45	<5	4.02	4	21	29	625	4.38	<10	1.01	1617	11	0.04	17	1980	576	15	<20	192	0.09	<10	73	<10	<1	278
14	G35489	1.4	1.24	50	50	<5	2.83	<1	20	51	591	3.63	<10	1.22	1038	26	0.03	35	2010	68	20	<20	201	0.12	<10	91	<10	4	74
15	G35490	1.1	1.60	45	65	<5	1.52	<1	30	46	569	4.14	<10	1.61	840	19	0.04	54	2140	58	10	<20	226	0.15	<10	115	<10	5	64
16	G35491	2.1	1.61	50	65	<5	6.71	6	20	45	904	4.17	<10	1.73	1565	27	0.02	34	2090	532	20	<20	423	0.12	<10	119	<10	4	344
17	G35492	<0.2	1.11	50	270	15	0.66	<1	7	98	6	2.28	<10	0.62	582	2	0.10	9	970	18	5	<20	91	0.16	<10	50	<10	3	49
18	G35493	2.0	1.67	50	40	<5	4.86	<1	25	53	818	4.63	<10	1.94	1345	14	0.03	41	1950	60	15	<20	456	0.15	<10	88	<10	1	84
19	G35494	2.6	1.42	50	40	<5	3.98	<1	22	60	1514	4.00	<10	1.41	970	10	0.03	43	2240	78	20	<20	416	0.12	<10	73	<10	3	84
20	G35495	1.3	2.01	55	35	<5	5.45	<1	15	47	848	3.96	<10	2.20	1418	15	0.02	48	1950	58	20	<20	617	0.12	<10	121	<10	2	76
21	G35496	1.2	1.31	45	55	<5	4.30	<1	21	48	711	3.93	<10	1.14	1156	16	0.03	21	2050	66	15	<20	231	0.10	<10	86	<10	2	66
22	G35497	0.9	1.27	40	60	<5	3.44	1	25	51	427	3.75	<10	1.28	1081	22	0.03	43	1970	52	20	<20	192	0.11	<10	103	<10	3	60
23	G35498	0.9	1.42	35	55	<5	3.46	<1	26	59	422	4.21	<10	1.43	1192	23	0.03	43	2350	54	20	<20	212	0.14	<10	109	<10	4	68
24	G35499	1.1	1.56	40	45	<5	4.57	1	25	57	497	5.07	<10	1.44	1569	28	0.03	40	1940	312	20	<20	192	0.14	<10	130	<10	2	134
25	G35500	0.6	1.78	40	80	15	7.53	<1	28	64	339	8.38	<10	1.81	1896	30	0.02	58	1400	56	5	<20	481	0.16	<10	317	<10	<1	72

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35501	2.4	1.62	40	110	<5	4.79	<1	23	67	1847	5.37	<10	1.50	1173	21	0.05	64	1650	62	15	<20	394	0.15	<10	264	<10	5	60
27	G35502	0.4	2.10	45	125	<5	5.02	<1	17	77	487	6.46	<10	1.97	1858	20	0.04	61	1700	66	25	<20	201	0.14	<10	350	<10	4	127
QC DATA:																													
Repeat:																													
1	G35476	1.9	2.01	50	60	10	5.53	2	21	66	409	5.50	<10	2.38	2581	16	0.04	29	1510	192	50	<20	301	0.14	<10	88	<10	7	127
11	G35486	1.2	0.71	55	50	10	2.00	<1	16	42	207	2.88	<10	0.51	737	8	0.05	7	1190	204	10	<20	136	0.06	<10	36	<10	3	77
Resplit:																													
1	G35476	2.0	1.86	50	45	15	5.98	<1	18	51	390	4.78	<10	2.01	2502	11	0.03	20	1550	206	20	<20	289	0.17	<10	79	<10	6	115
Standard:																													
Pb113		11.8	0.27	65	70	<5	1.75	42	3	7	2269	1.13	<10	0.13	1586	77	0.01	4	80	5418	30	<20	70	0.02	<10	11	<10	<1	7172

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/1578
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5596

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

11-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07117
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09107	0.91	0.027
2	X09108	0.64	0.019
3	X09109	0.72	0.021
4	X09110	0.55	0.016
5	X09111	0.78	0.023
6	X09112	0.58	0.017
7	X09113	0.49	0.014
8	X09114	0.53	0.015
9	X09115	0.39	0.011
10	X09116	0.46	0.013
11	X09117	0.55	0.016
12	X09118	0.52	0.015
13	X09119	0.37	0.011
14	X09120	0.51	0.015
15	X09121	0.25	0.007
16	X09122	0.41	0.012
17	X09123	0.29	0.008
18	X09124	0.46	0.013
19	X09125	0.34	0.010
20	X09126	0.59	0.017
21	X09127	0.40	0.012
22	X09128	0.38	0.011
23	X09129	0.36	0.010
24	X09130	0.26	0.008
25	X09131	0.38	0.011
26	X09132	0.39	0.011
27	X09133	0.48	0.014
28	X09134	0.46	0.013
29	X09135	0.49	0.014

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5596 11-Oct-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X09136	0.27	0.008
31	X09137	0.38	0.011
32	X09138	0.40	0.012
33	X09139	0.37	0.011
34	X09140	0.44	0.013
35	X09141	0.46	0.013
QC DATA:			
Repeat:			
1	X09107	0.81	0.024
10	X09116	0.40	0.012
19	X09125	0.38	0.011
Resplits:			
1	X09107	0.80	0.023
Standard:			
SI25		1.79	0.052

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5596

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07117
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09107	0.9	0.70	5	20	<5	2.62	1	12	81	1221	4.12	<10	0.69	335	124	0.03	6	910	46	<5	<20	222	0.02	<10	13	<10	<1	135
2	X09108	0.9	0.81	15	25	<5	2.20	<1	12	108	1207	3.87	<10	0.60	314	107	0.03	6	940	52	10	<20	128	0.02	<10	15	<10	<1	88
3	X09109	1.2	0.57	<5	20	<5	1.02	3	16	113	1307	4.25	<10	0.42	291	106	0.03	7	1090	110	10	<20	25	<0.01	<10	10	<10	<1	170
4	X09110	0.4	0.87	20	25	<5	1.93	<1	13	73	837	4.09	<10	0.72	363	112	0.04	5	940	42	10	<20	104	0.02	<10	11	<10	<1	154
5	X09111	0.7	0.60	15	25	<5	2.00	2	12	93	920	4.20	<10	0.63	504	249	0.03	5	800	56	<5	<20	89	0.02	<10	9	<10	<1	99
6	X09112	0.5	0.66	10	25	<5	1.73	2	12	61	819	4.15	<10	0.66	398	174	0.04	5	900	38	10	<20	63	0.02	<10	9	<10	<1	97
7	X09113	0.4	0.72	5	25	<5	2.64	<1	12	65	914	3.85	<10	0.74	446	87	0.03	2	810	40	<5	<20	115	0.02	<10	10	<10	<1	100
8	X09114	0.4	0.60	20	35	<5	1.40	1	14	62	816	4.46	<10	0.64	377	85	0.04	8	940	28	15	<20	29	0.02	<10	9	<10	<1	81
9	X09115	0.7	0.52	15	10	<5	1.56	1	15	98	877	4.63	<10	0.63	488	112	0.05	8	980	332	<5	<20	28	0.02	<10	8	<10	<1	66
10	X09116	1.4	0.62	55	30	<5	1.00	<1	13	91	838	3.67	<10	0.54	289	232	0.04	6	940	62	10	<20	48	0.02	<10	9	<10	<1	87
11	X09117	2.1	0.50	15	30	<5	0.69	1	14	82	775	4.09	<10	0.23	204	173	0.04	4	1150	42	<5	<20	42	0.02	<10	8	<10	<1	115
12	X09118	12.9	0.53	30	30	<5	0.86	2	15	101	936	4.87	<10	0.42	539	132	0.04	7	1080	116	10	<20	63	0.02	<10	10	<10	<1	178
13	X09119	2.9	0.54	15	30	<5	0.69	<1	15	85	703	4.43	<10	0.39	525	70	0.03	5	890	38	<5	<20	19	0.03	<10	8	<10	<1	117
14	X09120	5.8	0.41	105	30	<5	1.37	3	18	138	1006	6.39	<10	0.56	1032	226	0.03	15	990	168	30	<20	31	0.04	<10	10	<10	<1	129
15	X09121	3.0	0.36	55	40	<5	5.60	2	8	159	388	3.64	<10	2.43	5236	87	0.03	11	750	164	25	<20	76	0.06	<10	11	<10	5	97
16	X09122	2.4	0.74	15	25	<5	0.79	2	16	133	868	5.37	<10	0.79	619	86	0.03	13	790	134	15	<20	13	0.03	<10	18	<10	<1	136
17	X09123	3.2	1.03	40	45	<5	0.97	1	21	55	2593	3.49	20	0.54	189	193	0.03	9	370	66	<5	<20	39	0.04	<10	44	<10	5	261
18	X09124	1.3	1.38	20	30	<5	0.90	2	13	86	922	3.93	<10	1.51	627	164	0.03	9	1020	78	30	<20	18	0.02	<10	37	<10	<1	204
19	X09125	0.5	1.47	20	25	<5	1.28	<1	12	120	716	4.39	<10	1.38	622	125	0.03	6	1060	72	10	<20	31	0.02	<10	41	<10	<1	125
20	X09126	0.7	1.30	10	30	<5	1.59	2	15	71	802	4.60	<10	1.15	674	89	0.03	9	910	100	20	<20	33	0.02	<10	33	<10	<1	144
21	X09127	0.5	0.97	15	25	<5	2.15	1	14	68	577	4.13	<10	0.78	648	51	0.03	8	1100	68	15	<20	143	0.02	<10	21	<10	<1	156
22	X09128	0.3	0.87	15	25	<5	3.04	<1	12	94	514	3.33	<10	0.67	561	86	0.03	6	1120	56	5	<20	250	0.02	<10	16	<10	<1	95
23	X09129	0.5	0.87	20	25	<5	2.97	2	14	90	726	4.56	<10	0.87	1142	140	0.03	11	1050	104	20	<20	220	0.02	<10	19	<10	<1	161
24	X09130	0.4	0.49	20	15	<5	2.08	1	11	115	467	3.16	<10	0.30	463	166	0.04	9	1040	70	<5	<20	266	0.02	<10	9	<10	<1	128
25	X09131	0.9	0.94	30	25	<5	1.79	2	14	80	481	3.92	<10	0.80	1008	95	0.04	3	1480	68	5	<20	111	0.03	<10	16	<10	2	246

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09132	1.0	0.96	40	25	<5	1.23	<1	15	74	633	5.10	<10	0.84	1096	1724	0.05	4	1480	100	5	<20	37	0.03	<10	18	<10	3	192
27	X09133	0.7	1.00	30	25	<5	1.46	1	15	74	493	4.60	<10	0.93	1369	196	0.04	7	1330	84	10	<20	30	0.03	<10	18	<10	2	203
28	X09134	0.9	0.82	70	25	<5	1.02	2	15	95	627	4.34	<10	0.51	649	126	0.05	8	1560	110	10	<20	60	0.02	<10	15	<10	2	176
29	X09135	1.2	0.99	115	35	<5	0.93	3	18	92	736	5.04	<10	0.69	909	91	0.05	11	1470	188	35	<20	20	0.02	<10	21	<10	1	204
30	X09136	0.7	0.60	15	30	<5	0.46	2	18	100	619	4.94	<10	0.23	139	104	0.05	9	1620	136	<5	<20	13	0.02	<10	12	<10	<1	170
31	X09137	0.9	0.46	5	25	<5	0.33	2	17	95	613	4.46	<10	0.10	79	139	0.04	23	1150	68	<5	<20	18	0.02	<10	8	<10	<1	119
32	X09138	0.8	0.42	<5	20	<5	0.16	4	12	140	675	3.81	<10	0.10	84	101	0.04	12	470	70	<5	<20	25	0.01	<10	5	<10	<1	378
33	X09139	0.6	0.54	<5	25	<5	0.14	2	16	125	419	4.72	<10	0.23	158	88	0.03	17	450	48	<5	<20	5	0.02	<10	8	<10	<1	170
34	X09140	0.8	0.72	10	20	<5	0.32	2	17	125	505	4.51	<10	0.33	196	88	0.04	29	1130	70	<5	<20	7	0.02	<10	13	<10	<1	176
35	X09141	0.4	0.51	<5	20	<5	0.46	<1	19	73	544	4.81	<10	0.06	77	95	0.04	9	1610	20	<5	<20	42	0.02	<10	9	<10	<1	39
QC DATA:																													
Repeat:																													
1	X09107	0.8	0.63	5	20	<5	2.69	1	12	74	1250	4.04	<10	0.68	335	122	0.02	7	900	42	10	<20	244	0.01	<10	12	<10	<1	127
10	X09116	1.5	0.58	55	30	<5	0.99	2	13	81	818	3.60	<10	0.48	282	235	0.04	8	830	60	15	<20	43	<0.01	<10	8	<10	1	78
19	X09125	0.5	1.48	30	20	<5	1.28	1	13	110	704	4.30	<10	1.28	609	119	0.03	8	1080	76	15	<20	35	0.02	<10	36	<10	<1	119
Resplit:																													
1	X09107	1.0	0.65	15	15	<5	2.68	1	14	89	1215	4.27	<10	0.67	331	106	0.02	8	850	50	5	<20	213	0.02	<10	11	<10	<1	136
Standard:																													
Pb113		11.3	0.21	45	55	<5	1.67	35	2	5	2178	1.04	<10	0.09	1483	69	0.02	3	70	5416	10	<20	89	<0.01	<10	7	<10	<1	7011

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5594
XLS/07

Eco Tech Laboratory Ltd.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5597

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07120
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35523	2.21	0.064
2	G35524	0.52	0.015
3	G35525	0.58	0.017
4	G35526	1.21	0.035
5	G35527	0.30	0.009
6	G35528	0.46	0.013
7	G35529	0.48	0.014
8	G35530	0.61	0.018
9	G35531	1.45	0.042
10	G35532	1.36	0.040
11	G35533	1.74	0.051
12	G35534	0.67	0.020
13	G35535	1.49	0.043
14	G35536	1.19	0.035
15	G35537	1.72	0.050
16	G35538	1.93	0.056
17	G35539	1.41	0.041
18	G35540	1.68	0.049
19	G35541	1.56	0.045
20	G35542	1.22	0.036
21	G35543	1.54	0.045
22	G35544	1.23	0.036
23	G35545	1.82	0.053
24	G35546	1.66	0.048
25	G35547	1.36	0.040
26	G35548	1.60	0.047
27	G35549	1.33	0.039
28	G35550	1.70	0.050

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5597 4-Oct-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	G35551	1.61	0.047
30	G35552	1.58	0.046
31	G35553	1.82	0.053
32	G35554	<0.03	<0.001
33	G35555	0.43	0.013
34	G35556	0.64	0.019
35	G35557	0.41	0.012

QC DATA:

Repeat:

1	G35523	2.30	0.067
10	G35532	1.48	0.043
19	G35541	1.66	0.048

Resplits:

1	G35523	2.40	0.070

Standard:

OXI54		1.87	0.055

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

4-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5597

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07120
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35523	6.4	0.32	10	35	<5	0.95	2	7	195	5739	5.81	<10	0.21	465	25	<0.01	8	<10	10	<5	<20	24	0.01	<10	97	<10	<1	19
2	G35524	2.2	1.15	15	50	<5	3.31	<1	11	73	1344	4.80	<10	0.93	1560	14	0.01	4	990	28	5	<20	114	0.04	<10	33	<10	1	57
3	G35525	3.1	0.83	<5	50	<5	0.94	1	17	111	1912	6.24	<10	0.56	651	17	0.01	4	870	40	<5	<20	28	0.04	<10	30	<10	<1	34
4	G35526	1.7	1.07	10	40	<5	1.03	<1	13	137	581	4.53	<10	0.83	686	15	0.01	7	620	26	5	<20	29	0.02	<10	40	<10	<1	37
5	G35527	0.9	1.26	10	105	<5	1.70	<1	7	116	582	3.53	<10	0.87	933	16	0.01	4	780	28	<5	<20	66	0.03	<10	35	<10	2	39
6	G35528	1.5	1.38	20	65	<5	1.33	<1	10	105	954	4.57	<10	0.94	886	23	0.01	5	720	30	5	<20	52	0.03	<10	57	<10	1	54
7	G35529	2.2	0.90	10	45	<5	1.24	<1	13	120	1197	4.14	<10	0.62	768	15	0.01	5	670	30	<5	<20	50	0.03	<10	35	<10	<1	58
8	G35530	2.0	1.72	15	65	<5	1.24	2	14	87	1727	6.28	<10	1.25	1036	24	0.01	8	740	34	10	<20	42	0.03	<10	90	<10	<1	107
9	G35531	9.4	0.41	15	70	<5	1.86	2	12	172	9135	5.36	<10	0.43	983	22	<0.01	7	<10	22	<5	<20	166	0.02	<10	82	<10	<1	47
10	G35532	5.0	0.75	10	45	<5	0.37	<1	12	163	4602	5.85	<10	0.55	509	20	<0.01	8	<10	20	<5	<20	24	0.03	<10	126	<10	<1	89
11	G35533	5.0	0.37	10	45	<5	0.43	1	10	199	3875	4.91	<10	0.27	418	13	<0.01	6	<10	14	<5	<20	23	0.03	<10	129	<10	<1	51
12	G35534	5.2	0.24	5	40	<5	0.14	1	13	236	4847	4.88	<10	0.14	195	19	<0.01	7	<10	12	<5	<20	15	0.02	<10	70	<10	<1	29
13	G35535	6.8	0.11	<5	40	<5	0.10	1	9	209	6798	4.14	<10	0.03	122	12	<0.01	6	<10	10	<5	<20	14	0.01	<10	82	<10	<1	20
14	G35536	5.6	0.40	<5	40	<5	0.21	1	14	185	5896	5.16	<10	0.22	290	11	<0.01	7	<10	14	<5	<20	28	0.02	<10	67	<10	<1	44
15	G35537	5.9	0.19	5	40	<5	0.13	1	10	223	6875	4.96	<10	0.09	196	13	<0.01	7	<10	8	<5	<20	11	<0.01	<10	99	<10	<1	21
16	G35538	6.2	0.25	<5	40	<5	0.17	1	10	219	6324	5.21	<10	0.13	198	10	0.01	6	<10	10	<5	<20	27	0.02	<10	93	<10	<1	23
17	G35539	3.7	0.43	15	130	<5	0.36	1	9	201	3042	5.79	<10	0.31	250	17	0.01	6	10	16	<5	<20	93	0.03	<10	166	<10	<1	33
18	G35540	5.9	0.24	<5	45	<5	0.29	1	11	187	6580	5.29	<10	0.15	194	14	<0.01	8	<10	14	<5	<20	27	0.02	<10	116	<10	<1	22
19	G35541	5.1	0.18	<5	60	<5	1.70	1	11	160	4623	5.40	<10	0.12	700	17	0.01	6	<10	12	<5	<20	121	0.02	<10	61	<10	<1	14
20	G35542	6.0	0.21	<5	50	<5	0.45	1	14	199	6535	6.44	<10	0.09	307	16	0.01	8	<10	12	<5	<20	45	0.02	<10	61	<10	<1	15
21	G35543	5.5	0.34	<5	40	<5	0.19	2	11	227	4674	5.95	<10	0.20	265	15	<0.01	8	<10	14	<5	<20	31	0.02	<10	145	<10	<1	26
22	G35544	3.2	1.08	<5	40	<5	0.56	1	9	186	2762	5.96	<10	0.76	587	11	<0.01	6	260	26	<5	<20	39	0.03	<10	112	<10	<1	58
23	G35545	4.6	0.49	25	40	<5	0.86	<1	10	220	4450	5.19	<10	0.37	524	13	<0.01	7	10	18	<5	<20	46	0.02	<10	128	<10	<1	26
24	G35546	4.5	0.26	15	40	<5	1.05	1	16	208	3255	6.43	<10	0.37	629	11	<0.01	7	<10	18	<5	<20	28	0.03	<10	103	<10	<1	14
25	G35547	5.0	1.08	5	55	<5	0.30	2	12	172	3323	7.71	<10	0.71	496	23	0.01	6	260	26	<5	<20	13	0.04	<10	135	<10	<1	40

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35548	4.8	0.35	20	45	<5	0.28	1	7	214	4482	5.21	<10	0.25	270	9	0.01	7	<10	16	<5	<20	14	0.02	<10	128	<10	<1	18
27	G35549	4.3	0.51	10	40	<5	0.41	<1	13	191	4162	5.67	<10	0.31	359	10	0.01	7	<10	14	<5	<20	22	0.03	<10	89	<10	<1	24
28	G35550	7.0	0.34	<5	45	<5	0.27	1	11	204	6722	5.30	<10	0.18	269	13	0.01	6	<10	12	<5	<20	13	0.01	<10	98	<10	<1	23
29	G35551	6.4	0.37	5	45	<5	0.33	2	13	204	5830	6.25	<10	0.21	320	11	<0.01	9	<10	14	<5	<20	18	0.02	<10	111	<10	<1	25
30	G35552	8.2	0.15	10	40	<5	0.23	<1	33	256	7716	4.74	<10	0.06	178	14	<0.01	7	<10	10	<5	<20	9	<0.01	<10	50	<10	<1	11
31	G35553	4.1	1.11	50	55	<5	1.05	2	22	63	8588	4.24	20	0.64	206	610	0.04	62	40	72	20	<20	55	0.05	<10	46	<10	6	79
32	G35554	<0.2	1.03	15	265	10	0.67	<1	7	94	9	2.20	<10	0.63	574	3	0.13	7	830	18	<5	<20	97	0.12	<10	50	<10	5	47
33	G35555	4.1	1.49	15	35	<5	1.12	6	23	83	789	6.56	<10	1.19	1297	59	<0.01	9	2180	170	<5	<20	32	0.04	<10	57	<10	<1	346
34	G35556	2.1	2.43	15	50	<5	0.98	<1	26	79	1212	6.15	<10	2.06	1670	86	<0.01	8	2380	76	<5	<20	40	0.05	<10	75	<10	2	241
35	G35557	1.7	1.97	15	50	<5	0.90	1	26	69	861	5.85	<10	1.69	1154	62	<0.01	5	1980	98	<5	<20	50	0.04	<10	68	<10	1	222
QC DATA:																													
Repeat:																													
1	G35523	6.6	0.33	15	35	<5	0.96	<1	9	187	5802	5.82	<10	0.21	476	22	<0.01	6	<10	14	<5	<20	32	0.02	<10	92	<10	<1	17
10	G35532	4.9	0.72	15	50	<5	0.37	2	12	154	4495	5.74	<10	0.54	500	21	<0.01	8	<10	20	<5	<20	25	0.02	<10	119	<10	<1	88
19	G35541	4.8	0.18	5	60	<5	1.71	1	11	152	4561	5.37	<10	0.12	697	16	0.01	7	<10	10	<5	<20	126	0.02	<10	58	<10	<1	14
Resplit:																													
1	G35523	6.5	0.37	10	40	<5	1.05	1	10	195	5878	6.09	<10	0.24	464	23	<0.01	7	<10	14	<5	<20	23	0.02	<10	91	<10	<1	20
Standard:																													
Pb113		11.9	0.26	40	60	<5	1.71	40	2	6	2262	1.05	<10	0.11	1452	66	0.02	2	100	5536	25	<20	85	0.02	<10	9	<10	<1	6971

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl/nl
df/5591
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5598

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

9-Oct-07

No. of samples received: 30
Sample Type: Core
Project: KSM
Shipment #: 07119
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09142	<0.03	<0.001
2	X09143	0.35	0.010
3	X09144	0.34	0.010
4	X09145	0.40	0.012
5	X09146	0.39	0.011
6	X09147	0.21	0.006
7	X09148	0.31	0.009
8	X09149	0.31	0.009
9	X09150	0.36	0.010
10	X09151	0.44	0.013
11	X09152	0.37	0.011
12	X09153	0.47	0.014
13	X09154	0.40	0.012
14	X09155	0.33	0.010
15	X09156	0.34	0.010
16	X09157	0.58	0.017
17	X09158	0.58	0.017
18	X09159	<0.03	<0.001
19	X09160	0.54	0.016
20	X09161	0.54	0.016
21	X09162	0.39	0.011
22	X09163	0.52	0.015
23	X09164	0.53	0.015
24	X09165	0.99	0.029
25	X09166	0.32	0.009

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5598 9-Oct-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X09167	0.39	0.011
27	X09168	0.53	0.015
28	X09169	0.37	0.011
29	X09170	0.38	0.011
30	X09171	0.51	0.015

QC DATA:

Repeat:

2	X09143	0.37	0.011
10	X09151	0.42	0.012
19	X09160	0.49	0.014

Resplits:

2	X09143	0.35	0.010
30	X09171	0.49	0.014

Standard:

SI25		1.80	0.052

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
XLS/07

16-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5598

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 30
Sample Type: Core
Project: KSM
Shipment #: 07119
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09142	0.2	0.94	25	255	20	0.55	<1	7	97	5	2.25	<10	0.56	544	3	0.10	7	880	28	5	<20	70	0.09	<10	46	<10	3	56
2	X09143	1.4	0.53	<5	40	<5	0.41	5	18	96	492	5.63	<10	0.11	93	100	0.03	7	1890	38	<5	<20	35	0.02	<10	10	<10	<1	243
3	X09144	1.0	0.50	10	35	<5	0.43	<1	15	59	550	4.40	<10	0.17	113	97	0.03	6	2050	24	<5	<20	23	0.02	<10	9	<10	1	85
4	X09145	1.1	0.38	5	40	<5	0.48	2	21	54	694	5.15	<10	0.08	89	89	0.03	8	2300	24	<5	<20	22	0.02	<10	8	<10	<1	97
5	X09146	2.9	0.32	135	35	<5	0.30	3	15	95	542	4.89	<10	0.03	66	120	0.04	14	1180	102	40	<20	64	0.02	<10	5	<10	<1	145
6	X09147	1.5	0.46	105	40	<5	0.20	1	11	91	409	3.32	<10	0.15	71	106	0.03	11	920	108	25	<20	16	0.02	<10	6	<10	<1	91
7	X09148	0.8	0.48	15	30	<5	0.18	<1	12	130	392	4.33	<10	0.16	94	80	0.04	13	780	76	<5	<20	9	0.02	<10	9	<10	<1	75
8	X09149	1.0	0.36	20	35	<5	0.13	<1	11	112	324	3.82	<10	0.08	53	80	0.03	11	560	68	<5	<20	13	0.01	<10	4	<10	<1	36
9	X09150	2.1	0.33	15	35	<5	0.23	87	11	133	329	3.15	<10	0.07	52	94	0.03	19	1040	478	<5	<20	16	0.01	<10	6	<10	<1	3834
10	X09151	1.1	0.37	10	40	<5	0.29	2	18	135	497	5.06	<10	0.03	53	75	0.04	26	1330	64	<5	<20	22	0.02	<10	6	<10	<1	86
11	X09152	0.9	0.49	10	40	<5	0.39	<1	21	58	361	5.70	<10	0.09	63	80	0.05	44	1830	32	<5	<20	19	0.02	<10	10	<10	<1	39
12	X09153	0.5	0.50	20	30	<5	0.25	<1	21	57	452	4.66	<10	0.10	66	47	0.05	52	1160	20	<5	<20	16	0.01	<10	10	<10	<1	40
13	X09154	0.9	0.49	15	35	<5	0.63	<1	19	54	413	5.45	<10	0.07	78	143	0.06	6	3020	36	<5	<20	23	0.02	<10	9	<10	1	51
14	X09155	0.7	0.51	<5	30	<5	0.49	<1	18	51	444	5.42	<10	0.08	82	201	0.05	4	2360	46	<5	<20	17	0.02	<10	9	<10	<1	43
15	X09156	0.7	0.49	15	35	5	0.44	<1	18	57	323	5.26	<10	0.08	77	51	0.05	4	2110	34	<5	<20	24	0.02	<10	8	<10	<1	32
16	X09157	0.8	0.48	20	35	<5	0.47	<1	18	56	546	4.35	<10	0.06	71	79	0.05	3	2250	26	<5	<20	27	0.02	<10	7	<10	<1	24
17	X09158	0.6	0.47	15	35	<5	0.43	<1	18	52	456	4.37	<10	0.07	66	88	0.06	4	2030	24	<5	<20	27	0.02	<10	8	<10	<1	25
18	X09159	<0.2	0.99	20	265	15	0.57	<1	7	100	5	2.20	<10	0.57	558	2	0.11	6	880	26	<5	<20	85	0.10	<10	47	<10	4	53
19	X09160	0.5	0.48	5	30	<5	0.43	<1	15	44	333	4.27	<10	0.08	54	62	0.06	3	2050	20	<5	<20	22	0.02	<10	7	<10	1	25
20	X09161	0.7	0.40	<5	35	<5	0.38	<1	20	48	409	5.67	<10	0.04	52	66	0.05	3	1800	22	<5	<20	25	0.02	<10	6	<10	1	21
21	X09162	0.5	0.44	20	35	<5	0.40	<1	16	40	330	4.23	<10	0.07	62	66	0.05	3	1920	30	<5	<20	24	0.02	<10	7	<10	<1	22
22	X09163	0.7	0.51	15	30	<5	0.40	<1	17	49	427	4.78	<10	0.08	72	219	0.05	3	1920	26	<5	<20	26	0.02	<10	8	<10	<1	28
23	X09164	0.6	0.50	20	35	<5	0.46	<1	20	45	398	5.76	<10	0.07	56	82	0.07	6	2170	24	<5	<20	35	0.02	<10	11	<10	2	28
24	X09165	3.6	1.15	65	60	<5	0.73	3	17	54	3274	3.88	10	0.46	271	200	0.03	12	380	144	35	<20	33	0.04	<10	40	<10	6	184
25	X09166	0.5	0.43	25	30	<5	0.44	<1	16	51	294	4.30	<10	0.04	39	119	0.06	4	2070	18	<5	<20	24	0.02	<10	8	<10	1	18

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09167	0.5	0.39	20	35	<5	0.46	<1	17	57	303	4.94	<10	0.04	42	65	0.06	4	2200	18	<5	<20	24	0.02	<10	7	<10	1	22
27	X09168	0.8	0.37	10	35	<5	0.44	<1	18	65	394	5.02	<10	0.03	47	96	0.06	4	2080	18	<5	<20	28	0.02	<10	7	<10	2	23
28	X09169	0.6	0.51	10	40	<5	0.44	<1	18	61	414	5.12	<10	0.10	61	66	0.06	5	2070	22	<5	<20	27	0.02	<10	11	<10	2	43
29	X09170	0.6	0.41	15	35	<5	0.48	<1	19	54	393	4.56	<10	0.06	52	58	0.06	4	2290	18	<5	<20	27	0.02	<10	8	<10	2	30
30	X09171	0.5	0.42	10	40	<5	0.46	<1	19	62	456	5.13	<10	0.05	49	73	0.06	5	2180	20	<5	<20	25	0.02	<10	8	<10	<1	30
QC DATA:																													
Repeat:																													
2	X09143	1.5	0.45	<5	30	<5	0.42	6	18	101	508	5.76	<10	0.12	96	104	0.03	9	1920	38	<5	<20	30	0.02	<10	8	<10	<1	246
10	X09151	1.2	0.38	10	35	<5	0.29	2	19	139	503	5.11	<10	0.04	54	81	0.04	26	1350	62	<5	<20	18	0.02	<10	6	<10	<1	89
19	X09160	0.5	0.51	15	30	<5	0.43	<1	15	45	331	4.28	<10	0.09	58	64	0.06	3	2080	22	<5	<20	28	0.02	<10	8	<10	2	26
Resplit:																													
2	X09143	1.1	0.48	5	25	<5	0.49	4	17	78	489	5.20	<10	0.12	92	91	0.03	7	2007	36	<5	<20	27	0.02	<10	8	<10	<1	220
Standard:																													
Pb113		11.8	0.23	45	55	<5	1.71	36	3	6	2183	1.07	<10	0.10	1453	68	0.02	3	90	5576	20	<20	86	0.02	<10	8	<10	<1	6997

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/7387
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5599

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

15-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07121
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35558	1.06	0.031
2	G35559	0.58	0.017
3	G35560	0.37	0.011
4	G35561	0.31	0.009
5	G35562	0.26	0.008
6	G35563	0.32	0.009
7	G35564	0.41	0.012
8	G35565	0.24	0.007
9	G35566	0.36	0.010
10	G35567	0.34	0.010
11	G35568	0.38	0.011
12	G35569	0.44	0.013
13	G35570	0.27	0.008
14	G35571	<0.03	<0.001
15	G35572	0.55	0.016
16	G35573	0.56	0.016
17	G35574	0.99	0.029
18	G35575	1.03	0.030
19	G35576	0.86	0.025
20	G35577	0.49	0.014
21	G35578	0.61	0.018
22	G35579	0.47	0.014
23	G35580	0.40	0.012
24	G35581	0.45	0.013
25	G35582	0.49	0.014
26	G35583	0.57	0.017
27	G35584	0.36	0.010
28	G35585	0.13	0.004
29	G35586	0.07	0.002

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5599 15-Oct-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	G35587	0.05	0.001
31	G35588	0.08	0.002
32	G35589	0.09	0.003
33	G35590	0.06	0.002
34	G35591	0.04	0.001
35	G35592	0.04	0.001
QC DATA:			
Repeat:			
1	G35558	1.07	0.031
10	G35567	0.33	0.010
18	G35575	1.05	0.031
19	G35576	0.78	0.023
Resplits:			
1	G35558	0.91	0.027
Standard:			
SI25		1.79	0.052

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

18-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5599

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07121
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35558	1.8	2.07	65	50	5	1.70	1	26	86	613	7.86	<10	1.76	1961	49	<0.01	3	2490	58	10	<20	74	<0.01	<10	63	<10	6	328
2	G35559	3.3	1.89	80	45	10	1.16	1	21	66	746	7.74	<10	1.55	1125	200	<0.01	2	2970	98	10	<20	77	<0.01	<10	56	<10	8	193
3	G35560	1.7	1.35	25	40	<5	1.23	1	22	90	892	6.01	<10	0.98	845	48	<0.01	3	2590	50	<5	<20	56	<0.01	<10	44	<10	7	191
4	G35561	2.2	1.00	30	35	5	1.99	20	23	83	627	6.36	<10	0.69	869	47	<0.01	2	2080	408	<5	<20	60	<0.01	<10	28	<10	5	959
5	G35562	1.3	1.65	30	45	<5	2.04	1	16	94	560	6.35	<10	1.36	1134	59	<0.01	4	2360	78	5	<20	54	<0.01	<10	46	<10	6	314
6	G35563	1.7	0.94	45	35	<5	2.58	2	20	102	961	6.72	<10	0.67	925	53	<0.01	2	2080	78	5	<20	129	<0.01	<10	28	<10	5	160
7	G35564	1.9	1.12	30	40	<5	4.68	2	28	98	1204	7.16	<10	0.86	1129	61	<0.01	3	2020	114	5	<20	347	<0.01	<10	30	<10	5	260
8	G35565	1.2	1.44	30	35	<5	3.09	1	24	94	782	6.82	<10	1.11	1123	53	<0.01	3	2370	74	5	<20	138	<0.01	<10	46	<10	6	212
9	G35566	1.0	1.92	65	45	<5	1.93	2	22	71	802	7.56	<10	1.62	1544	53	<0.01	3	2280	36	30	<20	78	<0.01	<10	61	<10	5	279
10	G35567	0.7	1.88	40	45	5	1.17	<1	17	71	445	7.12	<10	1.57	1178	100	<0.01	2	2380	36	<5	<20	43	<0.01	<10	66	<10	5	301
11	G35568	1.7	1.44	30	40	<5	2.92	2	31	112	973	8.28	<10	1.09	1300	51	<0.01	4	2130	162	<5	<20	70	<0.01	<10	48	<10	5	141
12	G35569	1.1	2.47	30	55	<5	2.44	1	20	81	518	7.31	<10	2.01	1887	75	<0.01	3	2530	46	<5	<20	81	<0.01	<10	84	<10	6	250
13	G35570	3.1	1.19	40	50	<5	1.17	4	26	70	2596	3.54	20	0.53	225	200	0.02	15	610	74	10	<20	71	0.06	<10	47	<10	10	274
14	G35571	<0.2	1.05	10	300	<5	0.64	<1	9	77	5	2.90	<10	0.50	415	4	0.05	8	960	10	<5	<20	92	0.20	<10	48	<10	5	50
15	G35572	1.6	2.39	30	80	5	2.81	2	18	70	555	8.73	<10	1.87	2179	76	0.01	2	2480	48	<5	<20	93	<0.01	<10	79	<10	7	368
16	G35573	1.4	2.50	40	50	5	2.50	2	21	80	561	8.08	<10	1.99	2545	53	<0.01	2	2410	88	<5	<20	95	<0.01	<10	70	<10	6	307
17	G35574	2.0	2.56	40	50	<5	1.72	2	22	83	1087	8.33	<10	2.04	2274	119	<0.01	2	2300	90	<5	<20	73	<0.01	<10	77	<10	6	368
18	G35575	1.8	2.82	35	50	<5	1.03	1	26	73	1509	8.73	<10	2.23	1847	122	<0.01	2	2440	92	<5	<20	56	<0.01	<10	79	<10	5	357
19	G35576	2.4	2.70	35	40	<5	0.67	2	19	72	1094	7.77	<10	2.27	1230	154	0.01	2	2180	96	<5	<20	32	<0.01	<10	70	<10	4	289
20	G35577	1.4	2.93	40	55	<5	1.33	1	16	64	813	6.83	<10	2.73	1848	91	0.01	2	2100	56	<5	<20	80	<0.01	<10	83	<10	5	206
21	G35578	1.6	2.56	35	40	<5	1.21	1	25	59	921	6.28	<10	2.41	1519	42	0.01	3	1750	64	<5	<20	60	<0.01	<10	63	<10	4	250
22	G35579	1.3	2.11	30	35	<5	2.39	<1	18	64	777	5.90	<10	1.96	1188	115	0.01	2	1630	62	<5	<20	213	<0.01	<10	43	<10	3	262
23	G35580	1.5	1.85	25	35	<5	4.01	<1	15	66	513	4.75	<10	1.64	1216	94	0.01	2	1350	40	<5	<20	448	<0.01	<10	37	<10	2	113
24	G35581	0.8	2.11	25	35	<5	1.50	<1	12	62	534	4.69	<10	1.91	1085	115	0.01	2	1690	44	<5	<20	174	<0.01	<10	46	<10	3	273
25	G35582	1.7	0.82	15	25	<5	0.70	<1	16	92	1198	6.18	<10	0.65	619	50	0.02	3	1560	62	<5	<20	50	<0.01	<10	18	<10	3	111

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35583	1.2	1.41	15	25	<5	0.57	1	14	68	847	5.73	<10	1.28	791	61	0.02	2	1660	32	<5	<20	20	<0.01	<10	26	<10	4	148
27	G35584	1.3	1.34	15	25	<5	0.57	<1	15	53	917	6.22	<10	1.16	824	13	0.02	<1	1830	34	<5	<20	24	<0.01	<10	16	<10	4	172
28	G35585	1.3	0.57	10	30	5	0.29	<1	10	89	1285	7.27	<10	0.31	149	22	0.03	<1	1410	36	<5	<20	12	<0.01	<10	5	<10	2	43
29	G35586	1.1	0.63	10	25	<5	0.25	<1	12	88	1113	5.41	<10	0.37	114	52	0.03	<1	1210	18	<5	<20	14	<0.01	<10	4	<10	2	42
30	G35587	0.8	0.58	10	25	<5	0.29	<1	9	99	707	5.10	<10	0.30	97	20	0.03	1	1350	12	<5	<20	13	<0.01	<10	4	<10	2	34
31	G35588	1.2	0.64	15	25	<5	0.26	<1	10	118	1221	5.35	<10	0.36	119	26	0.03	1	1200	20	<5	<20	12	<0.01	<10	5	<10	1	45
32	G35589	1.1	0.56	25	25	<5	0.26	<1	11	120	1207	5.80	<10	0.26	96	64	0.03	1	1290	18	5	<20	12	<0.01	<10	4	<10	1	43
33	G35590	0.6	0.40	10	25	10	0.26	<1	12	109	687	6.94	<10	0.11	53	47	0.03	<1	1300	18	<5	<20	10	<0.01	<10	4	<10	1	17
34	G35591	0.5	0.35	10	25	15	0.24	<1	9	113	216	6.99	<10	0.07	39	47	0.03	<1	1190	16	<5	<20	12	<0.01	<10	4	<10	1	11
35	G35592	0.5	0.37	25	25	10	0.27	<1	11	106	443	6.89	<10	0.08	36	37	0.03	<1	1290	28	5	<20	13	<0.01	<10	4	<10	2	11
QC DATA:																													
Repeat:																													
1	G35558	1.8	2.16	65	45	<5	1.72	1	26	80	587	7.78	<10	1.70	1942	47	<0.01	2	2480	38	10	<20	71	<0.01	<10	61	<10	6	300
10	G35567	0.8	1.75	40	40	5	1.14	<1	17	69	432	7.21	<10	1.55	1195	95	<0.01	2	2360	36	<5	<20	43	<0.01	<10	65	<10	5	309
19	G35576	2.3	2.64	35	35	<5	0.68	2	19	67	1088	7.80	<10	2.27	1230	141	0.01	2	2190	98	<5	<20	30	<0.01	<10	68	<10	4	289
Resplit:																													
1	G35558	1.8	2.06	60	45	<5	1.54	<1	22	76	640	7.31	<10	1.90	1905	54	0.01	2	2290	52	5	<20	69	<0.01	<10	58	<10	5	301
Standard:																													
Pb113		11.6	0.26	60	60	<5	1.80	41	2	2	2242	1.10	<10	0.11	1500	56	0.01	1	100	5926	5	<20	79	<0.01	<10	6	<10	1	7148

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

JJ/jl
df/n5592S
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5603

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

16-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07122
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35593	0.05	0.001
2	G35594	0.13	0.004
3	G35595	0.10	0.003
4	G35596	0.10	0.003
5	G35597	0.07	0.002
6	G35598	0.21	0.006
7	G35599	0.16	0.005
8	G35600	0.16	0.005
9	G35601	0.20	0.006
10	G35602	0.18	0.005
11	G35603	0.13	0.004
12	G35604	0.23	0.007
13	G35605	0.14	0.004
14	G35606	0.21	0.006
15	G35607	0.78	0.023
16	G35608	0.20	0.006
17	G35609	0.20	0.006
18	G35610	<0.03	<0.001
19	G35611	0.27	0.008
20	G35612	0.21	0.006
21	G35613	0.18	0.005
22	G35614	0.16	0.005
23	G35615	0.22	0.006
24	G35616	0.38	0.011
25	G35617	0.40	0.012
26	G35618	0.33	0.010
27	G35619	0.44	0.013

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AK7-5603

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	G35620	0.18	0.005
29	G35621	0.21	0.006
30	G35622	0.90	0.026
31	G35623	1.49	0.043
32	G35624	0.68	0.020
33	G35625	0.55	0.016
34	G35626	0.59	0.017
35	G35627	1.00	0.029
QC DATA:			
Repeat:			
1	G35593	0.05	0.001
10	G35602	0.16	0.005
19	G35611	0.29	0.008
30	G35622	0.86	0.025
31	G35623	1.52	0.044
Resplits:			
1	G35593	0.06	0.002
Standard:			
Si25		1.80	0.052

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
XLS/07

18-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5603

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07122
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35593	0.5	0.36	25	25	10	0.24	<1	10	59	219	6.02	<10	0.06	27	105	0.03	<1	1310	44	5	<20	16	<0.01	<10	5	<10	3	21
2	G35594	0.5	0.44	15	20	<5	0.25	4	11	66	685	5.73	<10	0.07	35	29	0.03	<1	1390	18	<5	<20	15	<0.01	<10	4	<10	2	246
3	G35595	1.2	0.45	10	25	<5	0.39	6	11	64	1044	5.47	<10	0.09	40	61	0.03	<1	1880	32	<5	<20	15	<0.01	<10	4	<10	2	380
4	G35596	1.6	0.52	15	25	<5	0.53	12	8	54	1187	6.04	<10	0.10	41	32	0.03	<1	2540	48	<5	<20	18	<0.01	<10	6	<10	3	853
5	G35597	0.7	0.52	15	25	10	0.31	8	10	60	461	5.75	<10	0.13	43	39	0.03	<1	1490	76	<5	<20	14	<0.01	<10	6	<10	2	518
6	G35598	1.3	0.66	15	25	5	0.28	6	9	54	959	7.06	<10	0.23	73	33	0.03	<1	1360	106	<5	<20	14	<0.01	<10	8	<10	2	337
7	G35599	1.0	0.90	15	25	10	0.31	3	12	61	686	6.74	<10	0.38	120	65	0.03	<1	1500	182	<5	<20	14	<0.01	<10	8	<10	2	216
8	G35600	1.2	0.68	15	25	5	0.26	3	11	49	814	6.28	<10	0.23	79	34	0.03	<1	1420	120	<5	<20	15	<0.01	<10	6	<10	3	207
9	G35601	1.4	0.57	15	25	<5	0.60	3	10	69	988	5.34	<10	0.12	60	51	0.03	<1	2990	116	<5	<20	20	<0.01	<10	6	<10	4	195
10	G35602	1.2	0.87	15	25	<5	0.33	5	9	49	725	5.50	<10	0.31	114	36	0.03	<1	1560	68	<5	<20	18	<0.01	<10	8	<10	3	305
11	G35603	1.1	0.82	15	25	<5	0.32	3	9	58	730	5.33	<10	0.29	104	34	0.03	<1	1460	68	<5	<20	18	<0.01	<10	8	<10	3	237
12	G35604	1.0	1.11	15	25	<5	0.32	4	9	50	917	5.75	<10	0.46	159	45	0.03	<1	1460	66	<5	<20	16	<0.01	<10	11	<10	3	238
13	G35605	1.2	0.78	15	25	<5	0.33	5	9	56	874	5.59	<10	0.30	109	37	0.02	<1	1520	122	<5	<20	15	<0.01	<10	7	<10	3	267
14	G35606	1.4	0.95	15	30	<5	0.33	4	10	57	1158	5.52	<10	0.42	150	40	0.03	<1	1500	112	<5	<20	16	<0.01	<10	9	<10	3	199
15	G35607	1.0	1.80	20	40	<5	0.31	<1	11	34	853	5.56	<10	1.02	331	84	0.02	<1	1400	38	<5	<20	16	<0.01	<10	17	<10	3	148
16	G35608	1.2	1.41	15	30	<5	0.35	1	10	49	860	6.21	<10	0.77	247	83	0.03	<1	1690	36	<5	<20	19	<0.01	<10	12	<10	3	115
17	G35609	0.9	1.19	20	30	<5	0.53	1	10	51	870	6.41	<10	0.58	212	35	0.03	<1	2590	26	<5	<20	20	<0.01	<10	10	<10	4	94
18	G35610	<0.2	0.96	10	255	<5	0.55	<1	6	84	3	2.17	<10	0.58	547	<1	0.08	6	890	10	<5	<20	77	0.14	<10	40	<10	4	44
19	G35611	0.9	1.12	15	30	<5	0.29	1	9	42	782	5.25	<10	0.58	215	70	0.03	<1	1440	30	<5	<20	15	<0.01	<10	9	<10	2	107
20	G35612	0.7	1.27	15	30	<5	0.30	1	7	63	478	5.46	<10	0.79	287	44	0.02	<1	1430	34	<5	<20	16	<0.01	<10	10	<10	2	163
21	G35613	1.0	0.89	15	30	5	0.37	<1	11	58	814	7.16	<10	0.49	204	56	0.03	<1	1790	36	<5	<20	16	<0.01	<10	7	<10	2	92
22	G35614	1.5	1.01	15	30	<5	0.67	2	9	51	770	6.94	<10	0.51	282	39	0.03	<1	3470	62	<5	<20	19	<0.01	<10	9	<10	4	94
23	G35615	1.3	1.05	15	30	<5	0.40	<1	8	57	993	4.88	<10	0.50	272	66	0.02	<1	1960	32	<5	<20	15	<0.01	<10	10	<10	3	60
24	G35616	1.7	1.13	15	30	<5	0.39	1	11	65	1182	5.48	<10	0.61	263	76	0.02	<1	1810	56	<5	<20	16	<0.01	<10	9	<10	3	63
25	G35617	1.4	1.18	20	30	<5	0.54	<1	9	58	840	5.43	<10	0.73	288	260	0.02	<1	2650	36	<5	<20	16	<0.01	<10	11	<10	3	72

ECO TECH LABORATORY LTD.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35618	1.2	0.97	15	25	<5	0.38	<1	9	51	613	4.76	<10	0.53	213	52	0.02	<1	1730	20	<5	<20	16	<0.01	<10	9	<10	3	55
27	G35619	1.3	1.11	20	25	<5	0.34	<1	10	64	623	5.57	<10	0.73	286	48	0.02	<1	1570	30	<5	<20	15	<0.01	<10	9	<10	3	84
28	G35620	0.9	0.90	15	25	5	0.29	<1	9	48	609	5.82	<10	0.52	210	43	0.02	<1	1800	20	<5	<20	26	<0.01	<10	9	<10	3	57
29	G35621	1.2	0.62	10	20	<5	0.40	<1	8	67	725	4.79	<10	0.29	116	55	0.02	<1	1800	18	<5	<20	30	<0.01	<10	6	<10	3	31
30	G35622	4.9	0.52	85	25	<5	0.94	4	8	51	2147	6.94	<10	0.38	462	23	0.02	<1	1100	72	40	<20	38	<0.01	<10	5	<10	2	45
31	G35623	2.5	0.80	15	30	<5	2.10	1	9	60	1237	6.32	<10	0.80	795	23	0.02	<1	880	44	<5	<20	158	<0.01	<10	9	<10	3	50
32	G35624	5.1	1.36	15	30	<5	2.89	1	9	79	1703	4.38	<10	1.27	950	34	0.02	<1	960	32	<5	<20	227	<0.01	<10	21	<10	3	77
33	G35625	1.1	1.83	20	40	<5	2.05	<1	8	71	934	4.14	<10	1.60	827	42	0.02	<1	1120	18	<5	<20	216	<0.01	<10	28	<10	4	88
34	G35626	1.2	1.51	15	35	<5	2.28	<1	7	58	1278	3.73	<10	1.34	785	43	0.03	<1	1060	20	<5	<20	235	<0.01	<10	25	<10	3	85
35	G35627	3.7	1.10	70	65	<5	0.72	3	14	58	3120	3.90	20	0.51	286	207	0.03	17	410	128	30	<20	40	0.03	<10	38	<10	8	155
QC DATA:																													
Repeat:																													
1	G35593	0.5	0.40	25	25	10	0.28	<1	10	60	218	5.90	<10	0.06	26	110	0.03	<1	1300	36	<5	<20	16	<0.01	<10	4	<10	2	17
10	G35602	1.2	0.90	15	30	<5	0.34	4	9	51	724	5.52	<10	0.32	116	30	0.03	<1	1580	68	<5	<20	19	<0.01	<10	8	<10	3	308
19	G35611	1.1	1.17	15	35	<5	0.30	1	9	45	794	5.46	<10	0.59	220	73	0.03	<1	1460	28	<5	<20	15	<0.01	<10	11	<10	3	110
Resplit:																													
1	G35593	0.6	0.40	35	25	15	0.26	<1	11	63	226	7.00	<10	0.06	24	89	0.03	<1	1260	44	10	<20	15	<0.01	<10	5	<10	2	20
Standard:																													
Pb113		11.2	0.26	60	65	<5	1.71	41	2	<1	2216	1.10	<10	0.11	1505	66	0.01	<1	100	5402	5	<20	83	<0.01	<10	6	<10	1	6917

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5592
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5606

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

16-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07125
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	X09172	0.52	0.015		
2	X09173	0.45	0.013		
3	X09174	0.44	0.013		
4	X09175	0.53	0.015		
5	X09176	0.61	0.018		
6	X09177	0.31	0.009		
7	X09178	0.59	0.017		
8	X09179	0.35	0.010		
9	X09180	0.46	0.013		
10	X09181	1.84	0.054		
11	X09182	0.46	0.013		
12	X09183	0.47	0.014		
13	X09184	0.58	0.017		
14	X09185	0.77	0.022		
15	X09186	0.64	0.019		
16	X09187	0.47	0.014		
17	X09188	0.55	0.016		
18	X09189	0.72	0.021		
19	X09190	0.75	0.022		
20	X09191	0.62	0.018		
21	X09192	0.69	0.020		
22	X09193	0.42	0.012		
23	X09194	0.26	0.008		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5606

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
24	X09195	0.42	0.012	74.0	2.158
25	X09196	0.45	0.013		
26	X09197	0.51	0.015		
27	X09198	<0.03	<0.001		
28	X09199	<0.03	<0.001		
29	X09200	1.37	0.040		
30	X09201	0.51	0.015		
31	X09202	0.38	0.011		
32	X09203	<0.03	<0.001		
33	X09204	0.23	0.007		
34	X09205	0.24	0.007		
35	X09206	0.37	0.011		
QC DATA:					
Repeat:					
1	X09172	0.52	0.015		
11	X09182	0.49	0.014		
19	X09190	0.72	0.021		
29	X09200	1.40	0.041		
Resplits:					
1	X09172	0.48	0.014		
Standard:					
SI25		1.79	0.052		
Pb113				22.5	0.656

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
XLS/07

22-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5606

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07125
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09172	1.9	1.15	<5	70	<5	2.97	2	13	75	1213	3.82	<10	0.79	1059	40	<0.01	5	1420	34	5	<20	160	0.06	<10	31	<10	5	60
2	X09173	1.7	1.13	<5	135	<5	3.66	2	12	83	1435	3.73	<10	0.82	1224	47	0.02	5	1280	26	<5	<20	258	0.07	<10	33	<10	5	57
3	X09174	1.8	1.26	<5	125	<5	2.26	2	15	62	1386	4.38	<10	0.98	899	54	0.03	6	1440	22	<5	<20	193	0.07	<10	52	<10	5	56
4	X09175	1.7	1.14	<5	110	<5	2.47	2	14	84	1455	4.19	<10	0.87	985	29	0.03	6	1240	22	<5	<20	234	0.07	<10	45	<10	5	54
5	X09176	2.2	1.12	<5	145	<5	2.15	2	11	81	1652	4.14	<10	0.83	870	39	0.02	6	1270	18	<5	<20	188	0.06	<10	41	<10	5	60
6	X09177	1.2	1.10	<5	230	<5	2.49	2	11	62	1022	4.46	<10	0.82	1030	25	0.04	5	1400	14	<5	<20	223	0.07	<10	68	<10	4	56
7	X09178	1.8	1.14	<5	125	<5	1.90	2	15	89	1612	4.73	<10	0.90	805	47	0.04	6	1270	18	<5	<20	221	0.07	<10	73	<10	5	52
8	X09179	1.1	1.02	<5	160	<5	2.05	2	11	70	939	4.00	<10	0.76	759	30	0.03	7	1250	14	10	<20	252	0.05	<10	56	<10	4	40
9	X09180	1.6	1.05	<5	195	<5	2.22	2	14	84	1211	4.09	<10	0.82	778	30	0.05	6	1320	16	<5	<20	255	0.06	<10	73	<10	5	43
10	X09181	3.8	1.21	15	50	<5	1.13	4	24	60	8686	4.61	<10	0.70	227	613	0.05	67	80	64	25	<20	70	0.10	<10	49	<10	6	65
11	X09182	1.4	1.06	<5	80	<5	2.16	2	13	82	1227	4.29	<10	0.87	800	46	0.05	7	1360	18	10	<20	162	0.05	<10	81	<10	5	44
12	X09183	1.5	1.05	<5	130	<5	2.72	2	12	98	1212	3.61	<10	0.80	1077	47	0.03	6	1210	16	5	<20	382	0.05	<10	39	<10	4	45
13	X09184	1.7	1.33	<5	100	<5	2.17	2	14	70	1407	3.99	<10	1.08	1119	37	0.02	5	1320	20	10	<20	328	0.06	<10	40	<10	4	52
14	X09185	2.0	1.35	<5	115	<5	1.69	2	15	82	1885	4.54	<10	1.17	875	62	0.04	5	1280	18	10	<20	226	0.06	<10	63	<10	4	55
15	X09186	1.9	1.26	<5	105	<5	1.43	2	14	75	1650	4.60	<10	1.10	724	40	0.04	6	1260	16	5	<20	178	0.06	<10	73	<10	4	46
16	X09187	1.7	1.15	<5	125	<5	1.81	2	13	70	1740	4.33	<10	0.95	771	34	0.03	5	1220	16	<5	<20	240	0.06	<10	53	<10	4	44
17	X09188	1.8	1.03	<5	105	<5	2.92	2	14	58	1296	3.74	<10	0.75	1127	34	0.01	5	1310	18	5	<20	307	0.06	<10	31	<10	6	47
18	X09189	2.1	1.01	<5	130	<5	3.64	2	13	76	2111	3.48	<10	0.70	1330	56	0.01	5	1290	20	<5	<20	352	0.07	<10	27	<10	7	45
19	X09190	1.6	1.21	<5	70	<5	1.93	2	13	71	1681	3.58	<10	0.87	824	28	<0.01	5	1360	18	5	<20	168	0.05	<10	27	<10	4	54
20	X09191	1.4	1.16	<5	85	<5	2.27	1	13	71	1725	3.31	<10	0.81	916	42	<0.01	5	1390	20	10	<20	208	0.05	<10	27	<10	5	49
21	X09192	2.1	1.28	<5	60	<5	2.21	2	13	91	1842	3.71	<10	1.02	981	64	<0.01	6	1250	24	10	<20	202	0.05	<10	28	<10	4	51
22	X09193	1.7	1.24	<5	110	<5	3.15	2	15	68	1325	3.23	<10	0.97	1255	55	0.01	5	1380	20	10	<20	315	0.05	<10	26	<10	5	51
23	X09194	2.0	1.06	<5	120	<5	3.89	1	11	67	863	2.87	<10	0.76	1424	31	0.01	5	1410	18	10	<20	335	0.05	<10	22	<10	6	52
24	X09195	>30	0.92	35	45	<5	5.36	3	13	70	1496	3.28	<10	0.69	1760	33	<0.01	5	1420	136	10	<20	306	0.06	<10	22	<10	8	54
25	X09196	2.8	1.05	40	65	<5	3.09	2	13	65	1171	3.51	<10	0.77	1074	40	<0.01	5	1420	20	10	<20	216	0.05	<10	25	<10	5	41

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09197	14.7	1.67	185	60	<5	6.80	1	12	80	1569	4.51	<10	1.43	2465	43	0.02	5	1180	38	10	<20	329	0.08	<10	28	<10	7	64
27	X09198	0.8	3.50	15	120	20	4.98	3	35	52	20	7.07	<10	2.97	1727	9	0.01	7	1130	30	20	<20	324	0.12	<10	119	<10	7	83
28	X09199	0.2	3.12	30	90	30	6.58	2	35	46	9	6.26	<10	2.70	1755	6	0.02	6	1010	32	15	<20	429	0.13	<10	106	<10	7	76
29	X09200	9.2	1.44	130	55	<5	1.69	3	15	73	1555	4.38	<10	1.21	1001	41	<0.01	9	1590	50	25	<20	85	0.05	<10	27	<10	4	69
30	X09201	4.5	1.32	95	50	<5	2.85	2	16	55	882	4.09	<10	1.13	1388	32	<0.01	6	1610	30	10	<20	167	0.06	<10	28	<10	4	63
31	X09202	2.8	1.18	40	55	<5	3.61	2	12	76	1043	3.72	<10	0.95	1714	22	<0.01	6	1350	48	10	<20	245	0.06	<10	27	<10	4	80
32	X09203	<0.2	1.06	<5	265	15	0.65	<1	8	90	5	2.20	<10	0.66	590	4	0.13	7	960	18	<5	<20	87	0.14	<10	51	<10	3	40
33	X09204	1.2	1.41	15	140	<5	2.75	1	14	63	838	4.17	<10	1.04	1235	23	0.02	5	1600	24	10	<20	270	0.06	<10	40	<10	4	81
34	X09205	0.9	1.29	<5	120	<5	3.24	2	14	68	838	4.78	<10	1.00	1221	37	0.03	6	1560	20	<5	<20	371	0.07	<10	59	<10	4	59
35	X09206	1.5	1.13	5	105	<5	2.95	2	13	73	1487	3.81	<10	0.86	1226	33	0.01	5	1330	20	5	<20	300	0.06	<10	32	<10	4	53
QC DATA:																													
Repeat:																													
1	X09172	1.8	1.19	<5	80	<5	2.91	2	13	76	1218	3.76	<10	0.80	1046	43	0.01	5	1370	32	5	<20	164	0.06	<10	32	<10	5	57
19	X09190	1.5	1.31	10	70	<5	1.98	1	13	76	1745	3.69	<10	0.91	847	28	0.01	4	1400	20	<5	<20	179	0.06	<10	29	<10	4	55
Resplit:																													
1	X09172	1.7	1.19	<5	90	<5	3.07	2	13	75	1503	3.53	<10	0.84	1107	47	<0.01	5	1330	42	5	<20	187	0.06	<10	31	<10	6	61
Standard:																													
Pb113A		11.0	0.30	60	60	<5	1.71	48	3	6	2312	1.20	<10	0.12	1531	70	0.02	3	80	5472	10	<20	87	0.04	<10	9	<10	<1	7045

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5605
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5607 - Revised

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

26-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07124
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35663	0.63	0.018
2	G35664	0.69	0.020
3	G35665	1.63	0.048
4	G35666	0.94	0.027
5	G35667	0.96	0.028
6	G35668	0.71	0.021
7	G35669	0.91	0.027
8	G35670	1.15	0.034
9	G35671	0.68	0.020
10	G35672	0.65	0.019
11	G35673	0.52	0.015
12	G35674	0.54	0.016
13	G35675	0.53	0.015
14	G35676	0.34	0.010
15	G35677	0.54	0.016
16	G35678	0.54	0.016
17	G35679	0.70	0.020
18	G35680	0.28	0.008
19	G35681	0.62	0.018
20	G35682	0.61	0.018
21	G35683	0.53	0.015
22	G35684	0.47	0.014
23	G35685	0.57	0.017
24	G35686	0.67	0.020
25	G35687	0.69	0.020
26	G35688	0.53	0.015
27	G35689	0.92	0.027
28	G35690	<0.03	<0.001
29	G35691	0.62	0.018

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5607 - Revised 26-Oct-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	G35692	0.87	0.025
31	G35693	0.67	0.020
32	G35694	0.53	0.015
33	G35695	0.57	0.017
34	G35696	0.54	0.016
35	G35697	0.96	0.028
QC DATA:			
Repeat:			
1	G35663	0.61	0.018
3	G35665	1.71	0.050
8	G35670	1.16	0.034
10	G35672	0.61	0.018
19	G35681	0.67	0.020
Resplits:			
1	G35663	0.64	0.019
Standard:			
OXi54		1.82	0.053

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

25-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5607 - Revised

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07124
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35663	1.5	1.30	<5	40	<5	2.62	<1	10	79	1204	3.39	<10	1.01	923	34	0.03	3	920	24	5	<20	285	0.03	<10	26	<10	2	70
2	G35664	1.3	1.43	<5	60	<5	1.12	2	11	69	1270	3.75	<10	1.17	791	48	0.03	6	970	34	15	<20	88	0.03	<10	33	<10	3	75
3	G35665	2.0	1.32	<5	50	<5	1.67	<1	10	114	2156	3.70	<10	1.04	769	31	0.03	3	800	26	<5	<20	102	0.03	<10	23	<10	1	62
4	G35666	1.9	1.02	<5	40	<5	2.36	1	11	108	1532	4.21	<10	0.79	544	36	0.02	5	930	28	<5	<20	216	0.04	<10	20	<10	2	52
5	G35667	2.3	0.96	<5	40	<5	2.62	2	11	92	2355	3.82	<10	0.77	442	29	0.03	7	830	28	15	<20	305	0.02	<10	24	<10	2	44
6	G35668	1.4	0.93	5	35	<5	3.84	<1	10	79	1469	3.21	<10	0.69	1162	19	0.03	<1	910	16	<5	<20	326	0.07	<10	22	<10	3	51
7	G35669	6.0	0.43	30	45	<5	1.47	15	11	130	6146	6.38	<10	0.26	341	14	0.01	9	580	68	15	<20	150	0.02	<10	8	<10	<1	428
8	G35670	2.2	0.79	<5	50	<5	3.42	2	14	96	2377	4.52	<10	0.60	783	22	0.03	6	660	30	<5	<20	337	0.05	<10	28	<10	4	51
9	G35671	1.8	0.82	<5	40	<5	2.55	2	13	101	1618	3.38	<10	0.62	533	28	0.04	6	1020	28	<5	<20	280	0.04	<10	24	<10	5	52
10	G35672	1.9	0.89	10	20	<5	3.03	<1	11	83	1667	3.43	<10	0.65	577	61	0.04	2	1190	38	<5	<20	371	0.09	<10	23	<10	5	60
11	G35673	1.1	0.79	5	40	<5	2.72	1	10	72	1218	2.65	<10	0.57	464	37	0.03	5	1110	32	10	<20	346	0.06	<10	23	<10	6	55
12	G35674	1.5	0.68	5	30	<5	2.88	2	15	84	1159	3.42	<10	0.44	526	43	0.03	4	1070	44	<5	<20	322	0.08	<10	20	<10	5	50
13	G35675	1.6	0.76	5	45	<5	2.70	2	13	94	1110	3.76	<10	0.53	517	33	0.04	6	1090	36	10	<20	318	0.07	<10	23	<10	5	63
14	G35676	1.3	0.53	<5	35	<5	3.02	1	12	76	964	3.05	<10	0.31	427	27	0.03	3	960	46	<5	<20	342	0.07	<10	17	<10	5	36
15	G35677	1.5	0.69	<5	35	<5	2.10	2	12	82	1182	3.37	<10	0.46	387	24	0.03	5	980	32	<5	<20	235	0.07	<10	20	<10	4	44
16	G35678	1.2	1.00	10	110	<5	3.38	<1	12	81	1389	3.20	<10	0.63	772	24	0.05	1	1000	32	<5	<20	405	0.09	<10	27	<10	5	76
17	G35679	2.5	0.63	10	35	<5	2.98	7	11	101	1878	2.82	<10	0.44	559	26	0.03	5	770	90	<5	<20	341	0.06	<10	15	<10	4	278
18	G35680	3.2	1.17	30	60	<5	0.98	3	22	58	2688	3.42	20	0.64	191	198	0.04	11	520	70	20	<20	59	0.05	<10	47	<10	6	256
19	G35681	2.3	0.76	<5	30	<5	2.68	1	10	78	1889	3.30	<10	0.57	581	20	0.03	4	970	94	<5	<20	303	0.07	<10	24	<10	5	109
20	G35682	1.9	0.86	5	35	<5	2.96	1	12	101	1574	4.08	<10	0.60	651	18	0.03	5	950	40	<5	<20	380	0.08	<10	23	<10	5	101
21	G35683	1.8	0.90	15	30	<5	3.00	<1	13	126	1210	3.77	<10	0.54	628	22	0.04	3	1000	38	<5	<20	394	0.09	<10	25	<10	5	79
22	G35684	1.4	0.93	15	30	<5	3.90	2	11	102	1205	3.17	<10	0.69	939	29	0.04	7	980	28	20	<20	405	0.06	<10	31	<10	5	81
23	G35685	1.8	0.75	5	25	<5	3.29	1	11	102	1226	2.91	<10	0.49	648	28	0.04	3	1020	34	<5	<20	331	0.07	<10	22	<10	5	57
24	G35686	1.8	0.94	15	35	<5	3.17	1	11	93	1300	3.19	<10	0.60	704	26	0.04	4	1060	30	<5	<20	359	0.07	<10	27	<10	5	71
25	G35687	3.0	0.94	<5	35	<5	2.90	6	12	96	1544	3.13	<10	0.62	687	28	0.03	4	990	58	5	<20	357	0.08	<10	28	<10	4	172

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35688	1.8	1.08	5	30	<5	3.29	2	11	84	1091	3.46	<10	0.74	876	31	0.04	5	1090	34	5	<20	367	0.08	<10	31	<10	5	94
27	G35689	2.1	1.15	5	30	<5	4.26	3	12	88	1692	3.91	<10	0.83	869	26	0.04	7	950	38	20	<20	446	0.07	<10	34	<10	3	82
28	G35690	<0.2	1.16	10	275	20	0.68	<1	8	93	8	2.21	<10	0.62	549	2	0.14	5	910	28	<5	<20	89	0.13	<10	49	<10	5	41
29	G35691	1.3	1.08	10	40	<5	3.50	2	12	71	1245	3.68	<10	0.78	718	33	0.03	5	1020	34	10	<20	376	0.07	<10	34	<10	5	85
30	G35692	2.2	1.19	15	40	<5	3.06	2	14	90	1681	3.70	<10	0.82	714	28	0.05	5	1110	42	10	<20	357	0.09	<10	42	<10	6	124
31	G35693	3.1	0.94	20	35	<5	3.27	3	11	84	1310	2.99	<10	0.68	837	40	0.03	4	1120	36	10	<20	266	0.07	<10	22	<10	5	205
32	G35694	3.7	0.48	30	35	<5	3.27	3	11	84	1075	4.01	<10	0.22	981	20	0.02	5	1140	64	<5	<20	192	0.05	<10	12	<10	4	80
33	G35695	1.9	1.00	15	50	<5	2.45	6	13	96	1144	3.62	<10	0.72	694	37	0.03	8	1260	54	15	<20	237	0.05	<10	25	<10	8	265
34	G35696	1.8	0.85	30	30	<5	3.91	2	9	93	1159	2.87	<10	0.59	953	23	0.03	4	1060	38	<5	<20	264	0.04	<10	24	<10	4	125
35	G35697	3.3	0.52	15	40	<5	4.93	4	12	129	3005	3.94	<10	0.28	933	30	0.02	5	710	82	<5	<20	388	0.04	<10	15	<10	5	121
QC DATA:																													
Repeat:																													
1	G35663	1.4	1.29	<5	60	<5	2.58	1	11	79	1194	3.39	<10	1.00	917	33	0.03	4	960	30	10	<20	285	0.05	<10	26	<10	4	71
10	G35672	2.1	0.78	10	25	<5	2.79	1	10	75	1597	3.23	<10	0.58	536	68	0.03	4	1150	38	<5	<20	357	0.07	<10	22	<10	4	60
19	G35681	2.1	0.78	5	30	<5	2.85	1	11	81	1915	3.38	<10	0.59	602	24	0.04	6	1020	100	5	<20	334	0.08	<10	25	<10	6	112
Resplit:																													
1	G35663	1.3	1.31	5	40	<5	2.71	2	11	77	1157	3.54	<10	1.00	994	33	0.03	8	1010	30	5	<20	296	0.03	<10	28	<10	2	78
Standard:																													
Pb113A		10.8	0.28	60	55	<5	1.76	39	2	5	2245	1.07	<10	0.11	1460	79	0.02	2	100	5500	25	<20	86	0.01	<10	9	<10	<1	6969

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5607
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5608

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

26-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07126
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09207	0.45	0.013
2	X09208	0.79	0.023
3	X09209	0.62	0.018
4	X09210	0.33	0.010
5	X09211	0.56	0.016
6	X09212	0.56	0.016
7	X09213	0.38	0.011
8	X09214	0.47	0.014
9	X09215	<0.03	<0.001
10	X09216	0.41	0.012
11	X09217	0.33	0.010
12	X09218	0.49	0.014
13	X09219	0.40	0.012
14	X09220	0.56	0.016
15	X09221	0.37	0.011
16	X09222	0.43	0.013
17	X09223	0.79	0.023
18	X09224	0.43	0.013
19	X09225	0.30	0.009
20	X09226	0.53	0.015
21	X09227	0.41	0.012
22	X09228	0.34	0.010
23	X09229	0.56	0.016
24	X09230	0.44	0.013
25	X09231	0.50	0.015
26	X09232	0.71	0.021
27	X09233	0.35	0.010
28	X09234	0.49	0.014
29	X09235	0.51	0.015

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5608 26-Oct-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X09236	0.37	0.011
31	X09237	0.41	0.012
32	X09238	0.22	0.006
33	X09239	0.29	0.008
34	X09240	0.31	0.009
35	X09241	0.29	0.008
QC DATA:			
Repeat:			
1	X09207	0.50	0.015
10	X09216	0.39	0.011
Resplits:			
1	X09207	0.49	0.014
Standard:			
Oxi54		1.86	0.054

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

25-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5608

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07126
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09207	2.1	1.72	30	60	<5	1.63	2	13	111	1755	4.84	<10	1.53	1118	95	<0.01	9	1340	48	20	<20	146	0.04	<10	44	<10	2	64
2	X09208	3.4	0.98	15	60	<5	1.67	1	14	130	2756	3.98	<10	0.73	844	31	<0.01	6	750	32	<5	<20	156	0.03	<10	37	<10	<1	47
3	X09209	2.7	1.14	20	90	<5	1.64	<1	12	133	1823	3.85	<10	0.83	828	30	<0.01	7	1330	32	5	<20	125	0.03	<10	33	<10	2	62
4	X09210	2.3	1.06	10	100	<5	2.30	1	12	70	1410	3.71	<10	0.75	1015	28	<0.01	5	1540	30	5	<20	158	0.03	<10	34	<10	2	66
5	X09211	1.9	0.97	15	85	<5	1.80	1	13	84	1435	3.73	<10	0.63	833	26	<0.01	4	1580	32	<5	<20	174	0.03	<10	32	<10	3	59
6	X09212	2.2	1.04	10	85	<5	1.98	1	13	70	1915	4.46	<10	0.69	932	26	0.02	6	1570	30	<5	<20	160	0.04	<10	54	<10	2	62
7	X09213	1.2	1.02	10	270	<5	2.64	1	10	68	965	4.33	<10	0.74	1177	19	0.03	5	1640	28	<5	<20	335	0.04	<10	61	<10	4	64
8	X09214	1.8	1.20	<5	260	<5	1.96	3	11	63	1488	4.36	<10	1.04	1039	30	0.05	12	1520	24	25	<20	235	0.04	<10	83	<10	2	69
9	X09215	<0.2	1.12	15	285	15	0.66	<1	8	94	7	2.27	<10	0.63	563	<1	0.14	5	990	20	<5	<20	90	0.11	<10	52	<10	4	44
10	X09216	1.4	1.41	<5	175	<5	1.95	2	14	69	1112	5.26	<10	1.16	1188	32	0.03	7	1760	34	<5	<20	217	0.05	<10	81	<10	3	93
11	X09217	1.2	1.25	<5	225	<5	1.74	1	12	73	1088	4.41	<10	0.98	891	22	0.03	5	1710	32	<5	<20	201	0.04	<10	67	<10	2	78
12	X09218	1.4	1.65	15	145	<5	1.26	<1	13	87	1154	4.46	<10	1.48	918	30	0.02	6	1490	40	5	<20	116	0.04	<10	59	<10	2	87
13	X09219	1.6	1.52	15	125	<5	2.03	2	15	78	1199	4.37	<10	1.36	1233	38	0.01	8	1610	40	15	<20	190	0.04	<10	45	<10	3	80
14	X09220	1.9	1.25	10	125	<5	1.91	1	13	59	1502	4.35	<10	0.98	884	39	0.03	5	1540	32	<5	<20	206	0.04	<10	56	<10	3	74
15	X09221	1.4	1.19	5	120	<5	1.99	1	12	71	1251	3.96	<10	1.01	849	29	0.03	5	1580	44	5	<20	192	0.04	<10	61	<10	3	67
16	X09222	2.0	1.10	10	190	<5	1.95	2	12	65	1248	4.20	<10	0.83	794	26	0.04	4	1610	30	<5	<20	243	0.04	<10	62	<10	4	63
17	X09223	3.1	1.18	<5	120	<5	1.47	2	14	77	2399	5.13	<10	0.93	639	24	0.04	6	1430	38	<5	<20	195	0.04	<10	81	<10	2	71
18	X09224	1.9	1.16	<5	280	<5	1.79	1	11	69	1357	4.00	<10	0.96	776	36	0.05	5	1760	30	<5	<20	194	0.04	<10	82	<10	4	71
19	X09225	3.0	1.27	40	60	<5	1.03	3	22	63	2649	3.61	20	0.65	200	221	0.04	10	580	68	10	<20	58	0.05	<10	50	<10	6	274
20	X09226	1.8	1.37	5	265	<5	2.19	1	15	68	1520	4.17	<10	1.37	1061	36	0.05	6	1620	40	10	<20	267	0.05	<10	91	<10	7	80
21	X09227	1.5	1.29	<5	205	<5	2.47	2	17	72	1451	4.52	<10	1.15	955	32	0.05	7	1550	30	5	<20	356	0.03	<10	79	<10	5	76
22	X09228	1.4	1.79	10	190	<5	2.21	2	15	48	1154	4.27	<10	1.89	1350	35	0.03	7	1650	38	20	<20	232	0.04	<10	74	<10	6	89
23	X09229	2.8	1.09	20	50	<5	3.29	2	14	94	1887	3.37	<10	1.26	1799	34	0.01	3	1100	58	10	<20	288	0.04	<10	29	<10	4	53
24	X09230	2.5	1.14	20	90	<5	2.37	1	13	53	1389	3.47	<10	0.92	1182	24	0.02	5	1640	42	<5	<20	225	0.04	<10	36	<10	4	65
25	X09231	2.1	1.43	5	205	<5	1.69	1	13	87	1769	4.00	<10	1.32	827	51	0.04	7	1530	44	10	<20	229	0.04	<10	74	<10	4	81

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09232	3.4	1.37	20	65	<5	2.10	3	14	66	2011	4.14	<10	1.39	1361	24	0.02	8	1390	52	15	<20	196	0.04	<10	52	<10	4	71
27	X09233	1.5	1.40	20	140	<5	2.88	1	13	45	1041	3.09	<10	1.03	1274	25	<0.01	4	1620	38	15	<20	212	0.04	<10	31	<10	4	73
28	X09234	3.0	1.08	30	70	<5	4.56	10	10	69	982	3.08	<10	1.76	2951	36	<0.01	4	1270	392	15	<20	212	0.05	<10	26	<10	7	466
29	X09235	2.3	1.43	15	110	<5	2.61	2	12	76	1487	3.61	<10	1.12	1235	38	<0.01	7	1470	72	25	<20	217	0.03	<10	33	<10	3	119
30	X09236	1.8	1.18	<5	185	<5	2.89	2	13	45	1292	3.47	<10	0.78	1077	38	0.02	6	1680	34	5	<20	250	0.03	<10	39	<10	4	75
31	X09237	1.7	1.34	20	90	<5	3.85	2	13	67	1125	3.44	<10	0.91	1353	35	<0.01	4	1550	38	10	<20	202	0.03	<10	28	<10	4	82
32	X09238	1.3	1.26	20	200	<5	2.69	1	10	75	938	3.32	<10	0.90	1078	34	0.01	6	1440	38	5	<20	249	0.03	<10	32	<10	4	92
33	X09239	1.5	1.31	5	170	<5	1.67	3	11	86	1479	3.59	<10	1.06	936	36	0.02	6	1470	42	10	<20	181	0.03	<10	39	<10	3	97
34	X09240	1.6	1.24	20	100	<5	3.03	1	13	57	1128	3.71	<10	0.95	1305	35	0.01	6	1570	32	10	<20	250	0.04	<10	37	<10	5	81
35	X09241	1.4	1.24	20	60	<5	2.23	1	14	59	1091	3.10	<10	0.99	1187	37	<0.01	5	1650	40	<5	<20	138	0.03	<10	29	<10	5	72
QC DATA:																													
Repeat:																													
1	X09207	2.3	1.81	30	65	<5	1.69	<1	14	111	1915	4.99	<10	1.63	1167	90	0.01	5	1350	50	20	<20	151	0.05	<10	43	<10	4	64
10	X09216	1.1	1.31	<5	200	<5	1.85	3	13	65	1036	4.98	<10	1.11	1127	34	0.03	10	1690	32	5	<20	199	0.04	<10	77	<10	2	90
Resplit:																													
1	X09207	2.2	1.80	40	60	<5	1.68	2	14	97	1837	4.90	<10	1.62	1170	93	<0.01	11	1290	50	25	<20	155	0.05	<10	45	<10	2	67
Standard:																													
Pb113A		10.9	0.28	40	65	<5	1.67	40	3	6	2191	1.09	<10	0.11	1472	71	0.02	3	90	5454	20	<20	89	0.01	<10	10	<10	<1	6976

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5607
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5609

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

26-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07127
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09242	0.29	0.008
2	X09243	0.31	0.009
3	X09244	0.24	0.007
4	X09245	0.27	0.008
5	X09246	0.30	0.009
6	X09247	0.43	0.013
7	X09248	0.31	0.009
8	X09249	0.27	0.008
9	X09250	0.21	0.006
10	X09251	0.25	0.007
11	X09252	0.25	0.007
12	X09253	0.22	0.006
13	X09254	0.19	0.006
14	X09255	0.22	0.006
15	X09256	0.29	0.008
16	X09257	0.27	0.008
17	X09258	0.23	0.007
18	X09259	0.22	0.006
19	X09260	0.27	0.008
20	X09261	0.24	0.007
21	X09262	0.34	0.010
22	X09263	0.30	0.009
23	X09264	0.30	0.009
24	X09265	0.24	0.007
25	X09266	0.36	0.010
26	X09267	0.30	0.009
27	X09268	0.42	0.012
28	X09269	<0.03	<0.001

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5609 26-Oct-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	X09270	0.19	0.006
30	X09271	0.19	0.006
31	X09272	0.20	0.006
32	X09273	0.24	0.007
33	X09274	0.20	0.006
34	X09275	0.27	0.008
35	X09276	0.24	0.007

QC DATA:

Repeat:

1	X09242	0.27	0.008
10	X09251	0.25	0.007
19	X09260	0.30	0.009

Resplits:

1	X09242	0.25	0.007

Standard:

Oxi54		1.83	0.053

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

26-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5609

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07127
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09242	1.6	1.38	<5	195	<5	2.05	3	13	65	1245	3.94	<10	1.18	1039	29	0.03	8	1390	28	15	<20	226	0.04	<10	47	<10	4	89
2	X09243	1.2	1.20	<5	255	<5	2.17	3	12	93	1418	4.23	<10	1.05	945	27	0.03	7	1120	28	5	<20	330	0.05	<10	53	<10	4	79
3	X09244	1.5	1.34	5	175	<5	1.43	2	14	70	1259	3.75	<10	1.26	755	52	0.03	7	1430	28	10	<20	180	0.04	<10	51	<10	6	66
4	X09245	1.6	1.50	5	120	<5	1.44	2	13	63	1268	3.55	<10	1.57	1010	48	0.01	8	1340	30	20	<20	127	0.04	<10	44	<10	5	68
5	X09246	1.8	1.51	5	115	<5	1.37	2	13	63	1507	3.53	<10	1.55	956	50	0.01	5	1380	34	<5	<20	125	0.06	<10	40	<10	6	67
6	X09247	2.7	1.44	25	55	<5	2.69	2	18	72	1640	4.19	<10	1.62	1671	38	0.01	8	1320	50	15	<20	245	0.06	<10	34	<10	8	78
7	X09248	2.0	1.54	<5	80	<5	1.73	2	14	63	1471	3.93	<10	1.59	1165	47	0.02	7	1390	38	15	<20	169	0.05	<10	47	<10	6	81
8	X09249	1.8	1.55	<5	140	<5	1.60	2	14	71	1325	3.61	<10	1.54	1047	47	0.02	7	1380	38	10	<20	179	0.05	<10	47	<10	6	85
9	X09250	1.5	1.54	<5	225	<5	1.39	3	13	74	1198	3.72	<10	1.55	884	59	0.02	7	1350	34	15	<20	165	0.05	<10	57	<10	6	81
10	X09251	1.5	1.46	5	235	<5	2.00	1	11	80	1230	3.62	<10	1.56	1130	65	0.03	4	1290	30	<5	<20	239	0.06	<10	56	<10	6	62
11	X09252	1.4	1.46	<5	165	<5	1.71	3	14	67	1132	3.72	<10	1.44	1002	46	0.03	10	1360	32	25	<20	196	0.03	<10	57	<10	7	77
12	X09253	1.6	1.55	10	105	<5	1.86	3	14	71	1128	3.35	<10	1.54	1066	54	0.01	9	1410	50	30	<20	165	0.04	<10	41	<10	8	80
13	X09254	1.6	1.36	10	105	<5	1.87	2	15	88	1123	3.20	<10	1.18	861	86	0.02	7	1330	28	10	<20	184	0.04	<10	39	<10	6	70
14	X09255	1.5	1.31	5	145	<5	1.86	2	15	77	1030	3.33	<10	1.12	769	57	0.03	8	1400	32	15	<20	174	0.05	<10	48	<10	7	71
15	X09256	3.1	1.14	25	60	<5	0.94	3	21	58	2621	3.30	10	0.61	187	179	0.04	10	460	70	10	<20	61	0.06	<10	45	<10	7	262
16	X09257	1.9	1.24	5	150	<5	2.31	3	15	80	1286	3.78	<10	0.94	868	64	0.02	8	1380	28	10	<20	167	0.04	<10	48	<10	6	80
17	X09258	1.6	1.21	10	180	<5	2.50	3	14	64	1205	3.86	<10	0.99	957	58	0.03	9	1350	30	20	<20	191	0.04	<10	52	<10	6	82
18	X09259	1.7	1.02	10	135	<5	3.15	1	14	91	1112	2.82	<10	0.71	987	41	<0.01	7	1290	28	10	<20	165	0.03	<10	28	<10	7	55
19	X09260	1.9	0.82	<5	55	<5	4.91	3	15	65	1235	3.35	<10	0.57	1706	42	<0.01	9	1290	28	20	<20	217	0.04	<10	21	<10	8	46
20	X09261	1.8	0.93	10	85	<5	3.95	2	13	74	1157	2.86	<10	0.73	1375	38	0.01	7	1310	24	10	<20	221	0.04	<10	28	<10	7	70
21	X09262	1.8	0.90	<5	170	<5	2.24	2	11	113	1721	2.87	<10	0.68	782	34	0.02	7	1020	24	10	<20	169	0.03	<10	31	<10	5	58
22	X09263	1.6	1.22	10	145	<5	2.88	2	14	56	1191	3.16	<10	0.91	994	59	0.02	8	1350	34	15	<20	232	0.04	<10	38	<10	6	68
23	X09264	1.9	1.13	10	100	<5	5.19	2	13	53	1208	2.74	<10	1.11	1732	62	0.01	6	1350	24	10	<20	273	0.04	<10	29	<10	8	59
24	X09265	1.5	0.99	5	165	<5	3.51	1	12	79	978	2.54	<10	0.68	1115	44	0.01	5	1290	24	10	<20	212	0.04	<10	26	<10	6	53
25	X09266	3.1	1.15	10	65	<5	4.31	3	15	59	1124	3.09	<10	0.90	1572	60	<0.01	7	1440	68	20	<20	208	0.04	<10	29	<10	8	98

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007-5609 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09267	2.9	1.01	<5	75	<5	3.94	5	12	58	1214	2.75	<10	0.74	1225	46	0.01	6	1270	154	15	<20	261	0.03	<10	29	<10	6	242
27	X09268	2.9	1.13	5	65	<5	3.05	2	14	59	1237	3.18	<10	0.86	1180	68	0.02	7	1430	34	15	<20	229	0.04	<10	37	<10	7	64
28	X09269	<0.2	0.98	<5	255	20	0.58	<1	7	103	7	2.11	<10	0.59	527	3	0.10	7	890	22	<5	<20	87	0.12	<10	46	<10	2	40
29	X09270	1.7	1.32	<5	185	<5	2.01	1	13	71	975	3.49	<10	1.07	832	69	0.03	6	1430	28	10	<20	188	0.05	<10	51	<10	6	85
30	X09271	2.9	1.14	<5	160	<5	2.90	2	12	65	938	3.17	<10	0.88	1181	46	0.02	6	1420	28	10	<20	203	0.05	<10	38	<10	5	80
31	X09272	6.8	0.83	15	70	<5	>10	3	9	33	972	2.28	<10	0.56	3345	21	<0.01	4	1030	102	10	<20	299	0.06	<10	22	<10	9	110
32	X09273	2.9	1.03	10	120	<5	2.64	2	11	44	1470	2.40	<10	0.72	974	55	0.02	5	1360	34	10	<20	182	0.05	<10	32	<10	7	64
33	X09274	3.8	1.01	<5	75	<5	4.08	3	13	38	1168	2.85	<10	0.70	1405	86	0.02	6	1270	36	15	<20	271	0.05	<10	36	<10	5	75
34	X09275	1.6	1.07	<5	195	<5	1.86	1	11	48	1039	2.88	<10	0.83	682	69	0.04	4	1340	26	<5	<20	170	0.06	<10	62	<10	6	76
35	X09276	1.3	1.11	<5	275	<5	1.51	2	10	65	1274	3.23	<10	0.91	607	76	0.04	6	1260	28	10	<20	117	0.06	<10	67	<10	5	73
QC DATA:																													
Repeat:																													
1	X09242	1.5	1.42	<5	220	<5	2.02	3	13	68	1238	3.92	<10	1.19	1032	31	0.03	9	1400	30	20	<20	238	0.04	<10	49	<10	6	88
10	X09251	1.3	1.48	<5	245	<5	2.01	3	11	83	1207	3.64	<10	1.55	1131	71	0.03	7	1310	32	5	<20	238	0.05	<10	58	<10	6	63
19	X09260	1.7	0.86	<5	55	<5	4.88	3	15	66	1219	3.33	<10	0.57	1697	40	<0.01	8	1300	24	10	<20	213	0.06	<10	21	<10	8	46
Resplit:																													
1	X09242	1.5	1.36	<5	175	<5	1.95	3	14	60	1194	3.96	<10	1.12	942	31	0.03	9	1450	32	20	<20	215	0.04	<10	47	<10	4	91
Standard:																													
Pb113A		11.5	0.27	40	65	<5	1.62	37	2	5	2188	1.01	<10	0.10	1474	70	0.02	2	100	5426	20	<20	84	0.02	<10	8	<10	<1	6909

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5609
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5610

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

29-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07128
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	G35698	0.81	0.024		
2	G35699	1.45	0.042		
3	G35700	0.64	0.019		
4	G35701	0.72	0.021		
5	G35702	1.22	0.036		
6	G35703	0.87	0.025		
7	G35704	0.74	0.022		
8	G35705	1.46	0.043		
9	G35706	1.27	0.037	102	2.975
10	G35707	1.11	0.032		
11	G35708	0.66	0.019		
12	G35709	0.79	0.023		
13	G35710	1.03	0.030		
14	G35711	0.84	0.024		
15	G35712	0.83	0.024		
16	G35713	0.92	0.027		
17	G35714	0.68	0.020		
18	G35715	0.59	0.017		
19	G35716	0.05	0.001		
20	G35717	1.22	0.036		
21	G35718	0.66	0.019		
22	G35719	0.57	0.017		
23	G35720	<0.03	<0.001		
24	G35721	0.86	0.025		
25	G35722	0.69	0.020		
26	G35723	0.92	0.027		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AK7 - 5610

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
27	G35724	0.97	0.028		
28	G35725	0.81	0.024		
29	G35726	0.99	0.029		
30	G35727	1.41	0.041		
31	G35728	1.05	0.031		
32	G35729	0.87	0.025		
33	G35730	0.79	0.023		
34	G35731	1.07	0.031		
35	G35732	0.99	0.029		
QC DATA:					
Repeat:					
1	G35698	0.95	0.028		
5	G35702	1.39	0.041		
8	G35705	1.34	0.039		
9	G35706			96.5	2.814
10	G35707	1.13	0.033		
19	G35716	0.05	0.001		
20	G35717	1.32	0.038		
30	G35727	1.42	0.041		
34	G35731	1.11	0.032		
Resplits:					
1	G35698	0.88	0.026		
Standard:					
OXI54		1.87	0.055		
Pb113				22.4	0.653

AU: 30g FA/AA-Finish

JJ/jl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

26-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5610

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07128
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35698	1.8	0.79	10	35	<5	1.57	1	12	46	2167	3.43	<10	0.42	421	36	0.02	4	1020	26	<5	<20	146	0.04	<10	21	<10	3	84
2	G35699	5.8	0.73	10	40	<5	1.16	2	13	81	3634	3.70	<10	0.45	474	20	0.02	6	870	30	<5	<20	84	0.04	<10	17	<10	3	93
3	G35700	1.8	0.94	<5	75	<5	1.21	2	9	113	1446	3.00	<10	0.73	710	24	0.02	7	1000	32	5	<20	81	0.03	<10	27	<10	1	87
4	G35701	1.8	1.02	<5	55	<5	0.39	2	11	111	1604	3.47	<10	0.87	491	22	0.03	8	1080	38	10	<20	55	0.04	<10	35	<10	<1	92
5	G35702	3.1	0.68	10	35	<5	0.38	2	10	124	3275	3.34	<10	0.48	271	14	<0.01	8	900	72	<5	<20	91	0.03	<10	20	<10	<1	72
6	G35703	2.5	0.89	10	50	<5	0.65	2	11	128	2006	3.10	<10	0.71	526	24	0.01	9	1030	56	10	<20	198	0.03	<10	23	<10	1	76
7	G35704	2.2	0.78	<5	45	<5	0.65	2	11	117	1904	3.50	<10	0.61	493	15	0.02	8	890	60	10	<20	112	0.03	<10	28	<10	<1	79
8	G35705	2.5	0.77	20	35	<5	0.57	3	12	106	1787	3.41	<10	0.63	581	20	0.01	11	1030	54	20	<20	61	0.02	<10	29	<10	<1	75
9	G35706	>30	0.69	165	35	<5	0.75	5	10	112	1977	3.58	<10	0.38	473	21	0.01	8	880	106	185	<20	49	0.04	<10	21	<10	1	135
10	G35707	4.1	0.58	50	35	<5	0.47	2	11	141	2040	3.59	<10	0.30	299	16	0.01	9	750	44	10	<20	37	0.03	<10	20	<10	1	41
11	G35708	1.9	0.95	<5	120	<5	0.86	1	11	121	1475	4.09	<10	0.66	520	25	0.02	7	1010	36	<5	<20	78	0.05	<10	41	<10	2	69
12	G35709	3.0	0.83	15	30	<5	0.45	2	12	114	1954	3.90	<10	0.49	391	17	<0.01	9	1030	30	10	<20	34	0.03	<10	23	<10	<1	60
13	G35710	2.6	0.84	10	45	<5	0.37	3	10	116	2066	3.41	10	0.50	261	21	0.01	6	620	16	<5	<20	23	0.02	<10	17	<10	<1	35
14	G35711	2.5	0.89	<5	55	<5	0.52	1	10	110	2394	3.15	<10	0.53	328	22	0.01	3	510	16	<5	<20	38	0.02	<10	17	<10	1	49
15	G35712	3.2	0.74	<5	50	<5	0.64	3	15	95	2163	4.76	10	0.41	348	23	0.01	7	660	36	<5	<20	31	0.03	<10	14	<10	<1	43
16	G35713	2.7	0.83	<5	45	<5	0.70	2	10	110	2540	3.04	<10	0.57	422	23	0.01	5	580	12	<5	<20	37	0.01	<10	19	<10	<1	61
17	G35714	2.6	0.89	<5	45	<5	0.66	2	9	99	2029	3.46	<10	0.70	498	17	0.01	5	660	10	<5	<20	59	0.02	<10	20	<10	<1	56
18	G35715	1.8	1.13	<5	115	<5	1.02	2	9	101	1811	3.47	10	0.99	443	25	0.04	7	750	8	5	<20	135	0.03	<10	41	<10	1	103
19	G35716	0.2	0.07	<5	235	<5	8.05	<1	<1	127	158	0.78	<10	0.38	3026	1	0.02	<1	20	<2	<5	<20	1264	0.08	<10	2	<10	24	3
20	G35717	2.3	1.10	<5	55	<5	0.94	2	12	108	2243	3.89	10	1.01	598	32	0.03	8	710	8	5	<20	89	0.02	<10	35	<10	<1	67
21	G35718	2.0	0.91	<5	75	<5	0.73	<1	10	109	1878	3.27	<10	0.76	410	24	0.03	3	740	10	<5	<20	79	0.03	<10	38	<10	1	46
22	G35719	1.4	1.06	<5	55	<5	0.50	2	9	124	1327	3.78	10	1.00	370	24	0.03	9	920	14	10	<20	67	0.11	<10	46	<10	<1	52
23	G35720	<0.2	1.04	<5	245	10	0.56	<1	6	92	8	1.98	10	0.62	492	<1	0.14	2	710	10	<5	<20	102	0.18	<10	44	<10	7	39
24	G35721	2.5	0.95	<5	55	<5	0.55	1	11	107	2273	3.83	<10	0.84	297	25	0.03	6	680	18	<5	<20	73	0.02	<10	43	<10	<1	49
25	G35722	2.0	0.96	<5	65	<5	0.90	2	11	111	2212	3.85	<10	0.92	386	21	0.03	5	660	12	<5	<20	86	0.02	<10	46	<10	<1	42

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35723	2.2	1.10	<5	55	<5	0.37	1	11	103	2258	3.91	<10	1.08	334	44	0.03	7	710	14	5	<20	97	0.02	<10	39	<10	<1	54
27	G35724	1.8	1.00	<5	60	<5	0.32	3	11	103	1896	3.77	<10	0.98	286	40	0.02	11	610	16	30	<20	119	0.02	<10	40	<10	<1	48
28	G35725	2.4	0.90	<5	55	<5	0.30	8	10	76	2314	3.87	<10	0.78	240	21	0.02	5	580	42	<5	<20	87	0.02	<10	29	<10	<1	98
29	G35726	2.3	1.06	<5	60	<5	0.45	15	10	82	2787	3.63	<10	0.99	385	23	0.03	7	580	20	10	<20	89	<0.01	<10	38	<10	<1	151
30	G35727	2.1	0.89	<5	45	<5	0.27	4	10	100	2584	3.85	<10	0.73	282	11	0.02	2	500	30	<5	<20	35	0.03	<10	31	<10	<1	103
31	G35728	3.0	1.18	<5	60	<5	0.32	11	11	71	2833	5.24	10	1.05	345	19	0.02	9	600	24	15	<20	66	0.02	<10	35	<10	<1	108
32	G35729	6.6	0.59	<5	40	<5	0.36	2	9	94	3632	3.42	<10	0.36	241	10	0.01	5	430	20	<5	<20	26	<0.01	<10	19	<10	<1	38
33	G35730	3.1	0.90	<5	45	<5	0.29	2	9	88	2677	3.75	<10	0.73	297	13	0.02	5	560	28	<5	<20	38	0.01	<10	33	<10	<1	64
34	G35731	2.6	0.89	<5	45	<5	0.39	2	11	111	2277	3.90	<10	0.84	361	22	0.02	7	610	26	<5	<20	57	0.05	<10	33	<10	<1	70
35	G35732	3.6	1.13	15	65	<5	0.61	4	14	56	3375	3.75	20	0.51	226	204	0.03	11	300	130	35	<20	36	0.04	<10	39	<10	6	140
QC DATA:																													
Repeat:																													
1	G35698	1.9	0.74	10	25	<5	1.56	<1	11	44	2162	3.36	<10	0.39	417	24	0.02	<1	980	18	<5	<20	137	0.06	<10	19	<10	1	82
10	G35707	4.2	0.58	10	40	<5	0.42	4	10	121	2170	3.36	<10	0.34	269	14	0.01	11	630	30	15	<20	32	<0.01	<10	16	<10	<1	36
19	G35716	0.3	0.06	<5	205	<5	8.00	<1	<1	117	147	0.77	<10	0.36	2973	2	0.02	<1	30	<2	<5	<20	1173	0.07	<10	2	<10	23	3
Resplit:																													
1	G35698	2.0	0.71	<5	40	<5	1.28	3	10	56	2235	3.23	<10	0.49	334	19	0.02	8	970	20	5	<20	131	<0.01	<10	16	<10	2	74
Standard:																													
Pb113A		11.5	0.25	45	55	<5	1.64	32	2	4	2295	1.09	<10	0.10	1415	67	0.02	3	90	5518	25	<20	83	<0.01	<10	6	<10	<1	6985

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5609
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5611

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

26-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07129
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35733	1.05	0.031
2	G35734	0.74	0.022
3	G35735	1.22	0.036
4	G35736	1.16	0.034
5	G35737	0.86	0.025
6	G35738	0.57	0.017
7	G35739	0.73	0.021
8	G35740	1.19	0.035
9	G35741	0.78	0.023
10	G35742	1.15	0.034
11	G35743	0.93	0.027
12	G35744	0.65	0.019
13	G35745	0.59	0.017
14	G35746	0.60	0.017
15	G35747	0.93	0.027
16	G35748	0.81	0.024
17	G35749	1.02	0.030
18	G35750	1.00	0.029
19	G35751	0.67	0.020
20	G35752	0.84	0.024
21	G35753	0.67	0.020
22	G35754	0.84	0.024
23	G35755	0.84	0.024
24	G35756	0.82	0.024
25	G35757	0.60	0.017
26	G35758	0.95	0.028
27	G35759	1.16	0.034
28	G35760	1.00	0.029
29	G35761	0.83	0.024

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5611 26-Oct-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	G35762	0.72	0.021
31	G35763	1.01	0.029
32	G35764	0.66	0.019
33	G35765	1.23	0.036
34	G35766	1.81	0.053
35	G35767	<0.03	<0.001
QC DATA:			
Repeat:			
1	G35733	1.12	0.033
3	G35735	1.32	0.038
4	G35736	1.11	0.032
8	G35740	1.19	0.035
10	G35742	1.14	0.033
17	G35749	1.03	0.030
19	G35751	0.62	0.018
27	G35759	1.07	0.031
Resplits:			
1	G35733	1.11	0.032
Standard:			
Oxi54		1.83	0.053

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

26-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5611

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07129
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35733	2.6	0.94	<5	35	<5	0.39	2	13	105	3077	4.56	<10	0.81	353	26	0.02	9	930	34	10	<20	36	<0.01	<10	36	<10	<1	74
2	G35734	1.7	0.73	<5	35	<5	0.36	1	13	134	1712	4.21	<10	0.55	279	37	0.01	7	860	30	<5	<20	42	0.01	<10	25	<10	<1	52
3	G35735	2.3	0.88	<5	35	<5	1.19	2	12	113	2717	4.58	<10	0.81	482	18	0.02	9	860	30	10	<20	115	0.01	<10	39	<10	<1	62
4	G35736	2.4	0.52	5	35	<5	1.72	2	12	131	2585	4.44	<10	0.47	760	12	0.01	9	740	46	10	<20	109	0.01	<10	18	<10	<1	42
5	G35737	3.6	0.23	115	25	<5	1.22	3	12	149	2480	4.24	<10	<0.01	445	15	0.01	8	770	32	15	<20	48	<0.01	<10	10	<10	<1	41
6	G35738	1.2	0.74	<5	40	<5	0.91	1	12	132	1452	3.97	<10	0.54	475	26	0.02	7	930	24	<5	<20	80	0.01	<10	24	<10	<1	53
7	G35739	1.5	0.77	<5	35	<5	0.87	1	13	165	1898	4.11	<10	0.64	559	42	0.02	7	660	26	<5	<20	54	0.02	<10	28	<10	<1	56
8	G35740	2.5	0.98	<5	45	<5	0.60	2	15	114	2802	4.92	<10	0.84	517	34	0.02	7	1010	28	<5	<20	53	<0.01	<10	39	<10	<1	75
9	G35741	1.6	1.01	<5	50	<5	0.65	2	13	119	1561	4.51	<10	0.90	546	41	0.02	9	1070	24	10	<20	54	0.02	<10	43	<10	<1	82
10	G35742	1.9	0.64	<5	30	<5	0.34	1	10	138	2381	4.18	<10	0.47	232	23	0.02	7	780	30	<5	<20	36	<0.01	<10	27	<10	<1	38
11	G35743	1.7	0.49	<5	30	<5	0.31	2	11	147	2656	3.95	<10	0.32	182	27	0.02	9	730	24	<5	<20	29	<0.01	<10	19	<10	<1	26
12	G35744	1.3	0.72	<5	35	<5	0.42	1	10	108	1736	3.64	<10	0.51	286	37	0.02	7	1100	20	<5	<20	30	<0.01	<10	27	<10	<1	46
13	G35745	1.5	0.70	<5	40	<5	0.43	1	11	108	1872	3.56	<10	0.51	294	47	0.02	7	1070	22	<5	<20	34	<0.01	<10	27	<10	1	44
14	G35746	1.6	0.76	<5	35	<5	0.95	1	11	132	1821	3.88	<10	0.66	521	46	0.02	8	810	26	<5	<20	98	0.01	<10	30	<10	<1	48
15	G35747	1.5	0.69	<5	30	<5	1.56	2	11	149	2288	4.09	<10	0.60	460	40	0.02	8	810	26	<5	<20	279	0.01	<10	28	<10	<1	42
16	G35748	2.5	0.73	5	35	<5	0.98	1	11	130	2204	3.75	<10	0.68	614	34	0.01	8	890	28	<5	<20	49	0.01	<10	19	<10	1	38
17	G35749	3.4	0.66	<5	40	<5	0.69	2	14	144	2931	4.96	<10	0.46	426	28	0.01	9	880	28	<5	<20	37	0.01	<10	14	<10	<1	51
18	G35750	3.4	1.02	<5	35	<5	1.14	2	12	137	2729	4.16	<10	0.89	764	38	0.01	9	1030	28	15	<20	60	<0.01	<10	21	<10	1	67
19	G35751	3.4	1.21	15	50	<5	1.11	2	14	118	1648	4.97	<10	0.93	709	35	<0.01	8	1060	42	10	<20	62	0.02	<10	23	<10	<1	90
20	G35752	3.4	0.49	30	40	<5	1.33	3	18	94	1538	5.37	<10	0.43	754	26	<0.01	25	700	42	15	<20	49	0.02	<10	11	<10	<1	36
21	G35753	2.3	0.73	<5	45	<5	2.45	1	11	107	2313	3.78	<10	0.86	1608	42	0.01	8	1080	20	5	<20	88	0.02	<10	19	<10	3	42
22	G35754	2.3	0.80	<5	35	<5	1.35	2	14	123	2357	3.74	<10	0.78	874	31	0.01	9	930	22	10	<20	67	<0.01	<10	19	<10	2	58
23	G35755	2.0	0.87	<5	35	<5	1.41	2	13	102	2411	4.21	<10	0.92	866	33	0.02	7	990	24	10	<20	106	0.01	<10	30	<10	1	57
24	G35756	1.7	0.93	<5	35	<5	1.86	2	13	104	1905	4.11	<10	0.95	905	58	0.02	7	1070	26	10	<20	143	0.02	<10	32	<10	1	60
25	G35757	1.9	0.61	<5	35	<5	1.82	1	12	112	2077	3.74	<10	0.61	618	48	0.02	7	900	38	<5	<20	194	0.01	<10	25	<10	1	58

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007- 5611 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35758	2.3	0.90	<5	45	<5	1.46	2	14	116	2067	4.24	<10	0.96	783	37	0.03	7	1010	30	10	<20	127	0.02	<10	37	<10	1	72
27	G35759	2.2	0.53	<5	40	<5	1.45	2	16	125	2636	4.50	<10	0.48	699	25	0.02	7	780	40	<5	<20	91	0.01	<10	19	<10	<1	39
28	G35760	2.1	0.73	<5	40	<5	0.79	1	13	185	2108	4.44	<10	0.62	616	18	0.02	8	820	36	<5	<20	42	0.01	<10	25	<10	<1	58
29	G35761	2.1	1.07	<5	55	<5	0.38	1	12	157	2307	4.41	<10	0.92	385	41	0.02	8	900	20	<5	<20	77	<0.01	<10	43	<10	<1	87
30	G35762	2.3	0.78	<5	45	<5	0.38	2	14	139	2368	4.97	<10	0.64	390	19	0.02	9	700	42	5	<20	38	0.01	<10	28	<10	<1	75
31	G35763	2.2	0.81	<5	50	<5	0.95	2	14	138	2684	4.69	<10	0.73	493	19	0.03	9	760	28	5	<20	110	<0.01	<10	33	<10	<1	61
32	G35764	1.6	0.93	<5	55	<5	0.49	1	12	124	2108	4.32	<10	0.78	375	38	0.02	7	930	22	<5	<20	65	0.01	<10	36	<10	<1	56
33	G35765	2.8	1.08	<5	55	<5	1.29	4	14	83	3039	5.49	<10	1.07	977	27	0.02	11	670	34	20	<20	78	0.03	<10	32	<10	<1	67
34	G35766	3.7	1.08	20	55	<5	1.00	4	21	56	8671	4.03	20	0.63	200	554	0.04	63	<10	60	35	<20	57	0.02	<10	43	<10	6	65
35	G35767	<0.2	0.94	<5	255	20	0.53	<1	6	101	7	2.05	<10	0.58	515	2	0.09	3	900	16	<5	<20	66	0.10	<10	45	<10	5	48
QC DATA:																													
Repeat:																													
1	G35733	2.5	0.90	<5	40	<5	0.38	2	13	98	2944	4.40	<10	0.78	340	26	0.02	8	890	36	10	<20	37	<0.01	<10	34	<10	<1	72
10	G35742	1.8	0.63	<5	30	<5	0.34	<1	10	135	2368	4.07	<10	0.46	230	21	0.02	7	780	30	<5	<20	34	<0.01	<10	26	<10	<1	37
19	G35751	3.2	1.23	10	50	<5	1.14	2	14	117	1697	5.07	<10	0.96	725	36	<0.01	9	1080	40	15	<20	60	0.02	<10	23	<10	<1	91
Resplit:																													
1	G35733	2.4	1.04	<5	45	<5	0.40	4	12	104	3111	4.70	<10	0.90	377	29	0.02	10	950	34	15	<20	40	<0.01	<10	36	<10	<1	76
Standard:																													
Pb113A		11.4	0.26	55	60	<5	1.70	40	2	5	2311	1.01	<10	0.11	1499	70	0.02	4	90	5494	20	<20	91	<0.01	<10	8	<10	<1	7035

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5611S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5612

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

6-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07132
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	G35803	1.98	0.058		
2	G35804	4.10	0.120	76.3	2.23
3	G35805	2.85	0.083	242	7.06
4	G35806	1.21	0.035		
5	G35807	0.94	0.027		
6	G35808	1.12	0.033		
7	G35809	0.92	0.027		
8	G35810	0.30	0.009		
9	G35811	0.99	0.029		
10	G35812	1.02	0.030		
11	G35813	1.25	0.036		
12	G35814	1.07	0.031		
13	G35815	1.39	0.041		
14	G35816	1.11	0.032		
15	G35817	1.40	0.041		
16	G35818	0.76	0.022		
17	G35819	0.73	0.021		
18	G35820	<0.03	<0.001		
19	G35821	0.68	0.020		
20	G35822	0.83	0.024		
21	G35823	0.66	0.019		
22	G35824	0.59	0.017		
23	G35825	0.46	0.013		
24	G35826	0.84	0.024		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5612

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
25	G35827	0.68	0.020	74.5	2.173
26	G35828	0.87	0.025		
27	G35829	1.04	0.030		
28	G35830	0.75	0.022		
29	G35831	0.52	0.015		
30	G35832	0.97	0.028		
31	G35833	0.97	0.028		
32	G35834	0.70	0.020		
33	G35835	0.90	0.026		
34	G35836	1.62	0.047		
35	G35837	5.40	0.157		
QC DATA:					
Repeat:					
1	G35803	1.93	0.056		
2	G35804	4.20	0.122	75.0	2.187
3	G35805	2.70	0.079		
10	G35812	1.09	0.032		
11	G35813	1.26	0.037		
13	G35815	1.28	0.037		
19	G35821	0.63	0.018		
27	G35829	1.01	0.029		
34	G35836	1.80	0.052		
35	G35837	5.30	0.155		
Resplits:					
1	G35803	1.84	0.054		
Standard:					
Oxi 54		1.88	0.055		
Pb113				22.5	0.656

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
XLS/07

26-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5612

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07132
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35803	4.5	0.37	60	40	<5	1.33	2	13	135	2221	4.51	<10	0.25	479	43	0.01	8	900	18	20	<20	80	0.01	<10	10	<10	<1	23
2	G35804	>30	0.22	100	40	<5	1.26	8	11	127	2057	4.94	<10	0.02	494	37	0.01	8	590	652	110	<20	70	0.01	<10	8	<10	<1	282
3	G35805	>30	0.34	230	35	<5	0.29	15	12	155	3084	4.35	<10	0.10	129	54	0.01	6	680	302	375	<20	18	<0.01	<10	10	<10	<1	565
4	G35806	3.6	1.29	<5	45	<5	1.18	2	15	115	2635	4.37	<10	1.14	568	75	0.02	7	970	28	15	<20	91	0.01	<10	33	<10	2	49
5	G35807	2.5	1.11	<5	50	<5	1.48	2	13	101	2126	4.13	<10	1.02	462	68	0.03	7	1110	22	10	<20	132	0.01	<10	44	<10	3	59
6	G35808	2.4	1.08	<5	40	<5	1.10	2	15	106	2315	4.15	<10	1.02	563	72	0.02	8	930	22	10	<20	78	0.01	<10	36	<10	2	53
7	G35809	2.2	1.09	<5	40	<5	1.47	1	13	124	2022	3.77	<10	0.95	545	60	0.02	8	1030	20	10	<20	77	0.02	<10	37	<10	3	46
8	G35810	3.1	1.18	25	55	<5	0.96	3	20	58	2618	3.37	20	0.63	189	210	0.03	11	420	62	20	<20	52	0.02	<10	47	<10	7	265
9	G35811	2.4	0.91	<5	45	<5	1.42	1	14	117	1902	3.87	<10	0.72	478	74	0.03	8	1010	20	10	<20	114	0.01	<10	38	<10	2	48
10	G35812	2.7	0.84	<5	35	<5	1.57	2	13	139	2177	4.10	<10	0.72	346	65	0.03	8	880	24	5	<20	191	<0.01	<10	40	<10	3	38
11	G35813	2.9	0.82	<5	35	<5	0.77	1	14	115	2449	4.14	<10	0.71	286	87	0.02	7	910	22	<5	<20	50	<0.01	<10	31	<10	<1	39
12	G35814	2.0	1.21	<5	50	<5	1.29	2	14	130	2339	4.43	<10	1.09	389	78	0.02	8	1010	24	10	<20	79	0.01	<10	48	<10	2	48
13	G35815	2.5	0.91	<5	45	<5	0.88	2	15	102	2855	4.59	<10	0.81	301	107	0.02	6	850	26	5	<20	59	<0.01	<10	38	<10	1	31
14	G35816	4.1	1.00	<5	35	<5	0.83	1	15	115	2183	4.38	<10	0.89	323	71	0.02	7	1010	24	5	<20	51	0.01	<10	35	<10	2	50
15	G35817	4.1	1.33	<5	45	<5	1.21	2	14	97	2684	4.53	<10	1.18	517	73	0.03	8	1000	20	10	<20	66	<0.01	<10	54	<10	3	64
16	G35818	2.7	0.80	<5	40	<5	0.66	3	16	134	1978	5.08	<10	0.66	366	37	0.02	9	1040	42	5	<20	40	0.01	<10	28	<10	<1	77
17	G35819	2.9	1.07	<5	40	<5	1.44	2	13	103	1855	4.21	<10	0.90	394	47	0.02	10	900	26	5	<20	87	0.04	<10	38	<10	2	43
18	G35820	<0.2	1.05	<5	260	15	0.59	<1	6	111	9	2.10	10	0.59	528	1	0.12	4	890	16	<5	<20	87	0.11	<10	46	<10	6	38
19	G35821	3.3	1.16	<5	40	<5	1.78	2	14	127	1839	4.18	<10	1.01	544	69	0.02	7	1070	30	5	<20	94	0.01	<10	41	<10	3	73
20	G35822	3.3	1.13	<5	40	<5	1.98	6	14	131	1910	4.21	<10	0.98	587	73	0.02	9	1020	50	15	<20	103	0.01	<10	40	<10	4	196
21	G35823	3.1	0.99	<5	30	<5	1.62	2	13	120	1951	4.33	<10	0.85	440	54	0.02	8	950	22	5	<20	97	0.01	<10	32	<10	2	45
22	G35824	3.8	1.09	<5	35	<5	1.10	2	13	118	1916	4.27	<10	0.99	545	64	0.01	8	1140	34	5	<20	84	0.01	<10	31	<10	2	68
23	G35825	3.7	0.95	<5	25	<5	1.22	2	13	133	1869	4.45	<10	0.86	577	50	0.01	8	980	40	10	<20	76	0.01	<10	27	<10	1	45
24	G35826	7.2	0.64	15	35	<5	1.24	2	11	134	2117	4.16	<10	0.61	660	89	0.01	8	990	20	10	<20	73	0.02	<10	19	<10	2	31
25	G35827	>30	0.52	105	35	<5	1.37	3	13	138	3124	4.59	<10	0.61	884	53	0.01	6	1010	18	220	<20	65	0.01	<10	15	<10	2	52

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35828	25.0	1.10	60	50	<5	1.25	3	15	104	1890	6.19	10	1.23	1015	84	0.01	9	1490	30	115	<20	59	0.02	<10	26	<10	1	59
27	G35829	3.2	1.30	<5	40	<5	1.72	1	15	104	2321	4.08	<10	1.23	596	109	0.02	8	1130	22	10	<20	125	0.01	<10	46	<10	3	35
28	G35830	2.5	1.29	5	50	<5	1.49	1	12	101	1650	3.82	<10	1.19	503	60	0.02	7	1250	24	5	<20	121	0.01	<10	40	<10	3	43
29	G35831	6.1	1.27	20	45	<5	1.11	2	11	110	1696	3.75	<10	1.37	733	88	0.02	8	1400	22	20	<20	79	0.01	<10	42	<10	3	50
30	G35832	13.8	1.29	50	50	<5	1.62	3	16	83	1771	5.18	<10	1.56	1422	83	0.02	9	1400	30	30	<20	99	0.02	<10	41	<10	3	69
31	G35833	7.9	1.48	20	55	<5	1.60	2	15	117	2784	4.14	<10	1.41	717	91	0.02	7	1180	20	10	<20	138	<0.01	<10	50	<10	3	32
32	G35834	5.0	1.17	<5	45	<5	1.09	2	14	75	1901	4.07	<10	1.13	632	71	0.02	7	1280	26	10	<20	87	0.01	<10	42	<10	3	35
33	G35835	7.0	1.12	35	50	<5	1.04	3	16	127	2021	4.56	<10	1.10	722	191	0.02	10	1470	28	20	<20	70	0.01	<10	37	<10	3	45
34	G35836	5.0	0.87	15	40	<5	1.42	2	16	134	2352	3.76	<10	0.74	428	90	0.02	9	1060	26	10	<20	117	<0.01	<10	31	<10	2	30
35	G35837	4.7	0.81	75	45	<5	0.94	3	16	128	2078	3.76	<10	0.60	302	106	0.02	8	1190	34	15	<20	73	0.01	<10	27	<10	3	42
QC DATA:																													
Repeat:																													
1	G35803	4.6	0.41	55	35	<5	1.32	2	13	141	2171	4.44	<10	0.25	478	44	0.01	7	890	18	15	<20	79	<0.01	<10	12	<10	<1	23
10	G35812	2.7	0.87	<5	45	<5	1.53	2	13	146	2114	4.04	<10	0.71	334	65	0.03	10	860	24	5	<20	201	<0.01	<10	42	<10	2	38
19	G35821	3.4	1.22	<5	45	<5	1.80	2	13	136	1880	4.24	<10	1.04	563	72	0.02	7	1080	30	5	<20	95	0.01	<10	44	<10	3	73
Resplit:																													
1	G35803	4.6	0.42	55	40	<5	1.39	4	14	143	2210	4.46	<10	0.31	489	47	0.01	10	850	22	15	<20	88	0.01	<10	11	<10	<1	25
Standard:																													
Pb113A		10.9	0.26	40	65	<5	1.63	39	2	5	2277	1.01	<10	0.11	1480	70	0.02	4	80	5400	20	<20	100	<0.01	<10	8	<10	<1	6909

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5611S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5613

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07130
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35768	0.89	0.026
2	G35769	1.10	0.032
3	G35770	1.62	0.047
4	G35771	1.06	0.031
5	G35772	0.28	0.008
6	G35773	1.08	0.031
7	G35774	1.33	0.039
8	G35775	1.40	0.041
9	G35776	1.08	0.031
10	G35777	1.05	0.031
11	G35778	1.09	0.032
12	G35779	1.01	0.029
13	G35780	0.74	0.022
14	G35781	1.42	0.041
15	G35782	1.67	0.049
16	G35783	<0.03	<0.001
17	G35784	2.12	0.062
18	G35785	1.13	0.033
19	G35786	1.89	0.055
20	G35787	1.22	0.036
21	G35788	1.24	0.036
22	G35789	1.61	0.047
23	G35790	1.27	0.037
24	G35791	0.76	0.022
25	G35792	1.28	0.037

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AK7-5613 30-Oct-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	G35793	1.29	0.038
27	G35794	1.31	0.038
28	G35795	0.80	0.023
29	G35796	1.45	0.042
30	G35797	1.29	0.038
31	G35798	0.80	0.023
32	G35799	1.08	0.031
33	G35800	1.04	0.030
34	G35801	1.24	0.036
35	G35802	2.09	0.061

QC DATA:

Repeat:

1	G35768	0.86	0.025
3	G35770	1.58	0.046
7	G35774	1.27	0.037
8	G35775	1.40	0.041
10	G35777	1.12	0.033
14	G35781	1.41	0.041
15	G35782	1.50	0.044
17	G35784	2.30	0.067
19	G35786	1.84	0.054
22	G35789	1.53	0.045
26	G35793	1.34	0.039
29	G35796	1.43	0.042
35	G35802	2.20	0.064

Resplits:

1	G35768	0.91	0.027

Standard:

OXi54		1.89	0.055

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

26-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5613

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07130
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35768	1.8	0.94	<5	35	<5	0.73	1	12	109	2057	4.20	<10	0.68	576	24	0.01	7	860	24	10	<20	27	0.02	<10	19	<10	<1	53
2	G35769	2.1	1.35	<5	45	<5	0.48	2	13	117	2374	5.19	<10	0.92	529	24	0.01	10	1050	20	20	<20	18	0.02	<10	25	<10	<1	70
3	G35770	2.7	0.62	<5	30	<5	1.22	2	14	160	3931	4.34	<10	0.52	725	16	0.01	8	610	20	<5	<20	53	0.02	<10	16	<10	<1	36
4	G35771	1.8	1.20	15	50	<5	0.98	1	13	106	2119	4.34	<10	0.87	769	41	0.01	9	1200	22	10	<20	42	0.03	<10	23	<10	2	57
5	G35772	3.1	1.18	25	50	<5	1.00	3	21	54	2706	3.55	20	0.69	208	196	0.04	11	440	58	20	<20	58	0.03	<10	50	<10	6	271
6	G35773	2.0	1.03	<5	40	<5	0.38	1	16	119	2642	4.85	<10	0.61	379	34	0.01	8	1160	20	<5	<20	15	0.03	<10	19	<10	2	56
7	G35774	2.4	0.57	<5	35	<5	0.33	2	15	140	2687	4.45	<10	0.25	196	17	0.01	10	1010	36	<5	<20	14	0.02	<10	14	<10	<1	69
8	G35775	2.2	0.53	<5	30	<5	0.40	2	14	138	2469	4.27	<10	0.23	241	21	0.01	8	960	36	<5	<20	21	0.02	<10	13	<10	<1	60
9	G35776	2.4	0.75	15	35	<5	0.26	3	14	129	2576	5.16	<10	0.40	219	22	0.01	11	900	38	10	<20	12	0.02	<10	17	<10	<1	117
10	G35777	1.8	0.73	10	35	<5	0.30	2	12	133	2306	4.70	<10	0.41	249	21	0.01	10	1040	28	10	<20	11	0.02	<10	17	<10	<1	49
11	G35778	1.7	0.54	15	30	<5	0.29	2	15	117	2029	4.90	<10	0.24	182	30	0.01	11	990	20	10	<20	12	0.02	<10	14	<10	<1	32
12	G35779	2.0	0.91	<5	35	<5	0.79	1	14	130	2225	4.41	<10	0.68	595	29	0.01	8	1000	14	10	<20	36	0.02	<10	17	<10	<1	46
13	G35780	2.2	0.31	15	30	<5	0.50	1	13	118	2269	4.89	<10	0.07	261	32	0.01	8	860	22	<5	<20	21	0.02	<10	10	<10	<1	11
14	G35781	2.8	0.90	<5	30	<5	0.52	2	12	122	2445	4.52	<10	0.80	394	37	0.02	9	940	20	10	<20	40	0.02	<10	32	<10	<1	61
15	G35782	2.1	0.74	<5	50	<5	1.94	2	12	139	2335	4.10	<10	0.71	499	37	0.02	10	780	36	10	<20	213	0.02	<10	24	<10	<1	52
16	G35783	<0.2	1.08	<5	285	20	0.55	<1	6	94	9	2.17	<10	0.66	564	4	0.11	5	900	12	<5	<20	89	0.06	<10	49	<10	1	38
17	G35784	3.6	0.87	<5	30	<5	0.88	2	14	117	2915	4.23	<10	0.84	605	41	0.02	8	960	18	10	<20	42	0.02	<10	25	<10	<1	48
18	G35785	1.9	0.93	<5	45	<5	0.52	2	13	139	2326	4.54	<10	0.80	353	36	0.03	9	980	18	10	<20	37	0.02	<10	38	<10	<1	42
19	G35786	2.2	1.06	<5	50	<5	0.67	2	14	144	2971	4.70	<10	1.02	427	43	0.03	9	940	54	10	<20	70	0.02	<10	40	<10	<1	51
20	G35787	1.7	0.97	<5	40	<5	0.53	1	12	150	2171	4.15	<10	0.87	354	43	0.03	8	920	20	<5	<20	43	0.02	<10	37	<10	<1	60
21	G35788	1.2	1.03	<5	45	<5	0.61	1	13	119	2044	4.84	<10	0.95	380	37	0.04	8	1080	18	<5	<20	44	0.02	<10	50	<10	<1	63
22	G35789	1.8	0.84	<5	45	<5	0.52	2	14	99	2768	4.73	<10	0.70	244	72	0.03	10	1000	20	15	<20	47	0.02	<10	41	<10	<1	48
23	G35790	2.3	0.64	<5	35	<5	1.16	2	15	125	3337	4.48	<10	0.54	445	99	0.02	9	750	18	<5	<20	67	0.02	<10	22	<10	<1	26
24	G35791	1.5	0.93	<5	45	<5	2.53	2	12	106	2393	4.20	<10	0.90	397	50	0.02	8	930	20	10	<20	240	0.02	<10	36	<10	<1	35
25	G35792	1.4	0.59	15	35	<5	1.09	2	15	124	2435	4.58	<10	0.57	539	48	0.01	10	920	14	5	<20	31	0.02	<10	18	<10	<1	23

ECO TECH LABORATORY LTD. | ICP CERTIFICATE OF ANALYSIS AS 2007- 5613 | Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35793	1.9	0.70	<5	40	<5	1.23	2	12	100	2689	3.92	<10	0.75	640	51	0.01	8	860	14	10	<20	36	0.02	<10	21	<10	<1	27
27	G35794	1.7	0.75	<5	30	<5	2.41	1	13	117	2515	3.53	<10	0.78	513	42	0.02	7	970	14	<5	<20	218	0.02	<10	26	<10	1	29
28	G35795	1.3	0.93	<5	50	<5	2.35	2	13	86	1857	4.03	<10	0.99	677	38	0.02	6	1100	16	10	<20	187	0.02	<10	31	<10	2	42
29	G35796	2.3	0.66	<5	45	<5	2.33	2	15	115	3050	4.83	<10	0.67	429	40	0.03	8	660	18	<5	<20	231	0.02	<10	29	<10	<1	31
30	G35797	1.6	0.90	<5	30	<5	1.12	2	15	132	2631	4.41	<10	0.75	331	40	0.02	9	970	20	5	<20	74	0.02	<10	27	<10	<1	39
31	G35798	1.4	1.03	<5	45	<5	2.11	1	12	120	1725	3.71	<10	1.08	626	30	0.02	8	1100	22	10	<20	188	0.02	<10	30	<10	1	53
32	G35799	1.6	0.59	30	35	<5	1.86	2	15	114	1936	4.34	<10	0.52	564	40	0.01	10	1130	16	5	<20	119	0.02	<10	18	<10	2	23
33	G35800	1.7	0.58	15	35	<5	2.33	3	12	126	1801	3.35	<10	0.60	504	44	0.02	9	1040	18	15	<20	226	0.01	<10	18	<10	2	27
34	G35801	1.7	0.66	<5	30	<5	1.90	1	11	149	2258	3.96	<10	0.76	414	40	0.02	8	980	16	<5	<20	243	0.02	<10	26	<10	<1	33
35	G35802	2.2	0.61	20	40	<5	2.67	2	13	110	2022	4.16	<10	0.90	543	45	0.02	8	960	14	10	<20	388	0.02	<10	23	<10	1	37
QC DATA:																													
Repeat:																													
1	G35768	1.9	0.96	<5	40	<5	0.73	1	13	108	2120	4.23	<10	0.70	580	26	0.01	8	880	26	15	<20	28	0.02	<10	19	<10	<1	53
10	G35777	1.9	0.73	<5	30	<5	0.30	2	13	131	2343	4.76	<10	0.41	251	20	0.01	9	1040	28	5	<20	13	0.02	<10	17	<10	<1	48
19	G35786	2.0	1.06	<5	60	<5	0.67	2	14	143	2952	4.68	<10	1.01	425	41	0.03	9	940	52	10	<20	71	0.02	<10	40	<10	<1	51
Resplit:																													
1	G35768	2.0	0.99	<5	40	<5	0.67	2	13	130	2122	4.12	<10	0.71	509	27	0.01	9	920	20	15	<20	29	0.02	<10	20	<10	1	52
Standard:																													
Pb113A		10.9	0.26	50	40	<5	1.69	40	2	5	2351	1.05	<10	0.12	1495	73	0.02	3	90	5490	20	<20	90	<0.01	<10	8	<10	<1	6997

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
dl/5613
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5614

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

31-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07131
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09277	0.19	0.006
2	X09278	0.24	0.007
3	X09279	0.23	0.007
4	X09280	1.87	0.055
5	X09281	0.40	0.012
6	X09282	0.25	0.007
7	X09283	0.26	0.008
8	X09284	0.28	0.008
9	X09285	0.26	0.008
10	X09286	0.26	0.008
11	X09287	0.29	0.008
12	X09288	0.53	0.015
13	X09289	0.58	0.017
14	X09290	0.56	0.016
15	X09291	0.39	0.011
16	X09292	0.36	0.010
17	X09293	0.59	0.017
18	X09294	0.32	0.009
19	X09295	0.35	0.010
20	X09296	0.47	0.014
21	X09297	0.56	0.016
22	X09298	0.32	0.009
23	X09299	0.34	0.010
24	X09300	0.34	0.010
25	X09301	0.40	0.012

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7 - 5614

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X09302	0.39	0.011
27	X09303	<0.03	<0.01
28	X09304	0.46	0.013
29	X09305	0.39	0.011
30	X09306	0.26	0.008
31	X09307	0.19	0.006
32	X09308	0.09	0.003
33	X09309	<0.03	<0.01
34	X09310	0.21	0.006
35	X09311	<0.03	<0.01

QC DATA:

Repeat:

1	X09277	0.18	0.005
10	X09286	0.30	0.009
19	X09295	0.39	0.011

Resplits:

1	X09277	0.16	0.005

Standard:

OXI54		1.87	0.055

AU: 30g FA/AA-Finish

JJ/jl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

26-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5614

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07131
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09277	0.3	1.07	<5	355	<5	2.41	2	10	56	728	3.77	<10	0.91	828	71	0.05	5	1470	24	10	<20	254	0.04	<10	72	<10	4	65
2	X09278	0.6	1.26	<5	100	<5	1.59	2	12	78	1080	3.84	<10	1.12	708	53	0.04	7	1370	20	10	<20	130	0.03	<10	72	<10	5	86
3	X09279	1.0	1.15	<5	165	<5	4.00	2	13	58	1217	3.71	<10	0.96	1338	56	0.04	6	1450	12	10	<20	404	0.05	<10	63	<10	6	72
4	X09280	3.9	1.14	15	45	<5	1.04	3	21	55	8714	4.22	10	0.68	218	561	0.05	63	30	56	30	<20	58	0.02	<10	47	<10	5	62
5	X09281	1.4	1.10	<5	105	<5	1.92	3	14	102	1954	4.06	<10	0.94	794	33	0.04	7	1020	18	<5	<20	181	0.03	<10	76	<10	4	78
6	X09282	1.0	1.26	<5	140	<5	2.10	2	15	63	1234	3.73	<10	1.11	865	63	0.04	7	1480	22	10	<20	181	0.04	<10	65	<10	6	76
7	X09283	1.0	1.27	<5	110	<5	2.46	3	15	72	1558	3.51	<10	1.08	988	47	0.03	7	1500	22	10	<20	169	0.03	<10	53	<10	6	93
8	X09284	1.2	1.22	<5	100	<5	1.93	2	13	58	1328	3.27	<10	1.02	799	53	0.02	8	1470	24	15	<20	117	0.02	<10	43	<10	5	71
9	X09285	1.1	1.21	<5	150	<5	2.25	2	13	64	1232	3.34	<10	0.99	849	54	0.02	6	1410	18	10	<20	157	0.03	<10	41	<10	5	79
10	X09286	0.8	1.21	<5	260	<5	3.42	2	12	75	1295	3.53	<10	0.92	1100	47	0.02	7	1520	16	10	<20	235	0.03	<10	46	<10	7	59
11	X09287	1.7	1.06	10	80	<5	7.12	2	11	65	997	2.61	<10	0.83	2097	30	0.01	5	1260	48	10	<20	318	0.03	<10	24	<10	7	76
12	X09288	1.9	1.24	15	60	<5	2.71	2	15	71	2852	3.11	<10	1.03	990	32	0.01	7	1410	20	15	<20	136	0.02	<10	31	<10	6	69
13	X09289	1.8	1.21	20	70	<5	2.87	3	16	78	2452	3.05	<10	1.00	1039	34	0.01	8	1430	24	15	<20	145	0.03	<10	30	<10	8	76
14	X09290	2.4	0.82	15	45	<5	6.39	3	11	83	2001	2.91	<10	0.66	1957	81	0.01	5	1120	52	5	<20	233	0.03	<10	21	<10	6	97
15	X09291	2.3	1.30	<5	95	<5	2.49	2	13	81	2505	2.78	<10	1.05	982	97	0.01	6	1190	22	10	<20	143	0.02	<10	29	<10	6	64
16	X09292	1.4	1.28	<5	115	<5	3.32	2	13	64	1441	3.17	<10	0.99	1112	30	0.01	6	1340	16	10	<20	201	0.03	<10	30	<10	5	59
17	X09293	1.9	1.15	<5	105	<5	3.86	2	10	75	1650	2.34	<10	0.92	1275	62	0.01	5	1320	358	5	<20	202	0.03	<10	29	<10	6	64
18	X09294	2.0	1.33	5	75	<5	2.59	2	14	59	1506	3.04	<10	1.08	1097	65	0.01	6	1490	24	10	<20	148	0.02	<10	31	<10	6	79
19	X09295	1.0	1.53	<5	255	<5	1.77	2	13	67	1344	4.11	<10	1.27	899	65	0.04	7	1460	16	5	<20	164	0.03	<10	68	<10	5	71
20	X09296	0.9	1.34	<5	170	<5	1.94	2	13	70	1505	4.06	<10	1.09	824	36	0.03	7	1370	14	10	<20	169	0.03	<10	53	<10	5	57
21	X09297	1.6	1.34	<5	90	<5	1.81	1	11	81	2579	3.38	<10	1.10	725	19	0.02	6	1200	18	10	<20	124	0.03	<10	38	<10	5	52
22	X09298	1.1	1.36	<5	230	<5	2.98	2	13	67	1662	3.90	<10	1.14	1031	155	0.04	6	1390	18	10	<20	239	0.04	<10	60	<10	5	61
23	X09299	1.0	1.53	<5	230	<5	2.09	1	12	56	1786	3.87	<10	1.35	894	47	0.03	5	1490	18	<5	<20	152	0.03	<10	61	<10	6	72
24	X09300	0.8	1.49	<5	365	<5	1.49	2	11	63	1332	4.17	<10	1.34	836	53	0.04	6	1530	20	10	<20	125	0.04	<10	74	<10	5	80
25	X09301	1.1	1.31	<5	270	<5	1.73	2	12	65	1605	4.37	<10	1.11	815	24	0.04	7	1320	18	10	<20	124	0.04	<10	75	<10	4	74

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007- 5614 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09302	3.6	1.15	<5	60	<5	2.23	33	13	70	2122	3.89	<10	0.95	967	48	0.02	8	1130	76	15	<20	137	0.04	<10	45	<10	3	1623
27	X09303	<0.2	1.14	<5	290	10	0.57	<1	6	93	9	2.25	<10	0.68	575	2	0.13	7	940	10	<5	<20	91	0.07	<10	52	<10	2	41
28	X09304	0.8	1.36	<5	325	<5	2.48	2	11	65	1213	3.71	<10	1.14	969	42	0.04	6	1370	16	5	<20	150	0.04	<10	60	<10	5	86
29	X09305	1.6	1.62	<5	180	<5	1.73	3	14	78	1742	4.77	<10	1.41	986	28	0.03	9	1320	24	20	<20	100	0.04	<10	84	<10	6	98
30	X09306	1.9	1.70	<5	115	<5	1.80	2	14	55	1453	4.11	<10	1.55	1100	39	0.03	6	1370	60	10	<20	109	0.05	<10	76	<10	5	86
31	X09307	1.7	1.50	<5	150	<5	1.69	1	12	63	1163	3.55	<10	1.38	851	49	0.04	6	1230	22	<5	<20	84	0.04	<10	70	<10	4	72
32	X09308	1.4	2.11	<5	205	<5	2.92	<1	16	58	1286	4.29	<10	2.13	1248	32	0.05	15	1260	18	<5	<20	119	0.06	<10	98	<10	4	91
33	X09309	0.4	4.78	<5	75	10	1.84	2	41	168	191	7.26	<10	5.64	2162	14	0.04	106	710	26	30	<20	56	0.08	<10	191	<10	1	169
34	X09310	1.4	2.10	<5	120	<5	4.75	1	17	60	1185	4.19	<10	2.22	1182	23	0.05	14	1330	32	<5	<20	154	0.06	<10	124	<10	5	75
35	X09311	<0.2	4.09	10	240	15	5.89	2	37	163	94	5.07	<10	5.16	1806	10	0.03	91	600	24	35	<20	235	0.10	<10	130	<10	5	64
QC DATA:																													
Repeat:																													
1	X09277	0.5	1.08	<5	370	<5	2.46	2	11	55	750	3.82	<10	0.94	846	74	0.05	6	1520	26	10	<20	263	0.04	<10	73	<10	6	65
10	X09286	1.0	1.21	<5	240	<5	3.41	2	12	77	1312	3.53	<10	0.93	1104	44	0.02	7	1500	16	15	<20	240	0.02	<10	46	<10	6	58
19	X09295	1.1	1.45	<5	240	<5	1.68	2	12	63	1278	3.91	<10	1.21	853	59	0.04	6	1400	16	10	<20	152	0.03	<10	63	<10	5	68
Resplit:																													
1	X09277	0.4	1.12	<5	350	<5	2.45	2	10	56	743	3.60	<10	0.98	852	72	0.05	8	1510	22	10	<20	271	0.04	<10	70	<10	5	63
Standard:																													
Pb113A		11.0	0.28	40	50	<5	1.75	42	2	5	2352	1.09	<10	0.10	1558	71	0.02	5	90	5512	20	<20	86	<0.01	<10	9	<10	<1	6986

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5613
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5617

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

31-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07133
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09312	0.31	0.009
2	X09313	0.27	0.008
3	X09314	0.40	0.012
4	X09315	0.27	0.008
5	X09316	0.23	0.007
6	X09317	0.31	0.009
7	X09318	0.32	0.009
8	X09319	0.37	0.011
9	X09320	0.35	0.010
10	X09321	0.36	0.010
11	X09322	0.24	0.007
12	X09323	0.18	0.005
13	X09324	0.26	0.008
14	X09325	<0.03	<0.001
15	X09326	0.22	0.006
16	X09327	0.12	0.003
17	X09328	0.21	0.006
18	X09329	0.42	0.012
19	X09330	0.40	0.012
20	X09331	0.19	0.006
21	X09332	0.14	0.004
22	X09333	0.15	0.004
23	X09334	0.16	0.005
24	X09335	0.26	0.008
25	X09336	0.28	0.008

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7 - 5617

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X09337	0.13	0.004
27	X09338	0.14	0.004
28	X09339	0.20	0.006
29	X09340	0.22	0.006
30	X09341	1.58	0.046
31	X09342	0.52	0.015
32	X09343	0.28	0.008
33	X09344	0.10	0.003
34	X09345	0.13	0.004
35	X09346	0.19	0.006

QC DATA:

Repeat:

1	X09312	0.27	0.008
10	X09321	0.32	0.009
19	X09330	0.40	0.012

Resplits:

1	X09312	0.29	0.008

Standard:

OXI54		1.86	0.054

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
XLS/07

29-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5617

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07133
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09312	1.1	1.33	<5	135	<5	1.91	2	13	56	1144	3.85	<10	1.18	928	59	0.04	7	1300	18	10	<20	104	0.04	<10	71	<10	3	81
2	X09313	0.8	1.35	<5	345	<5	1.64	2	12	45	872	3.91	<10	1.15	843	50	0.04	6	1490	20	5	<20	114	0.04	<10	69	<10	5	79
3	X09314	1.4	1.25	<5	95	<5	1.73	2	12	63	1252	3.77	<10	0.99	945	128	0.02	5	1270	30	<5	<20	85	0.04	<10	47	<10	4	84
4	X09315	1.2	1.41	<5	160	<5	2.23	2	13	65	1135	4.04	<10	1.12	987	109	0.05	6	1500	20	10	<20	118	0.04	<10	71	<10	5	79
5	X09316	1.3	1.20	<5	155	<5	2.30	2	10	63	877	3.43	<10	1.00	1006	45	0.03	6	1340	30	<5	<20	125	0.04	<10	58	<10	4	92
6	X09317	1.1	1.25	<5	160	<5	2.33	2	14	52	992	4.01	<10	0.99	1004	35	0.04	5	1400	30	<5	<20	174	0.05	<10	65	<10	4	92
7	X09318	1.1	1.15	<5	395	<5	2.07	2	10	60	1224	4.13	<10	0.96	830	39	0.06	6	1400	18	<5	<20	156	0.05	<10	86	<10	4	77
8	X09319	1.8	1.29	<5	135	<5	2.45	2	12	69	1314	3.61	<10	0.98	1148	104	0.02	6	1400	28	10	<20	106	0.04	<10	48	<10	4	92
9	X09320	3.0	1.11	5	60	<5	2.58	1	13	81	1331	3.62	<10	0.82	1248	41	0.02	5	1190	50	<5	<20	102	0.04	<10	37	<10	4	67
10	X09321	2.0	1.01	<5	50	<5	2.13	3	12	48	1346	3.51	<10	0.72	830	59	0.02	5	1070	82	5	<20	91	0.04	<10	33	<10	3	82
11	X09322	1.2	0.93	<5	320	<5	2.20	2	8	52	1060	2.90	<10	0.65	694	54	0.04	5	1090	20	10	<20	167	0.04	<10	32	<10	4	64
12	X09323	0.9	0.90	<5	265	<5	2.44	1	8	57	834	2.72	<10	0.66	798	36	0.03	5	1060	18	10	<20	125	0.04	<10	30	<10	3	62
13	X09324	1.3	0.91	<5	110	<5	2.17	1	9	51	1228	2.48	<10	0.61	793	30	0.02	4	1090	18	<5	<20	83	0.04	<10	23	<10	4	61
14	X09325	<0.2	1.07	<5	265	15	0.56	<1	6	94	6	2.21	<10	0.64	573	4	0.12	7	900	12	5	<20	78	0.06	<10	50	<10	1	40
15	X09326	1.2	0.81	<5	100	<5	2.30	2	8	65	960	2.36	<10	0.47	741	23	0.02	4	1040	20	5	<20	115	0.04	<10	20	<10	4	57
16	X09327	0.8	0.78	<5	195	<5	3.26	<1	7	61	593	1.99	<10	0.47	909	25	0.02	2	1030	18	<5	<20	151	0.03	<10	20	<10	5	53
17	X09328	1.1	0.92	<5	130	<5	2.41	1	9	57	940	2.43	<10	0.66	858	99	0.02	4	1040	16	<5	<20	83	0.03	<10	25	<10	5	65
18	X09329	2.0	0.89	<5	55	<5	2.76	1	9	62	1467	2.89	<10	0.61	1007	46	0.01	4	1080	16	<5	<20	55	0.03	<10	26	<10	4	60
19	X09330	1.8	0.83	<5	70	<5	2.95	2	10	64	1524	2.70	<10	0.55	990	49	0.02	5	960	42	5	<20	60	0.03	<10	27	<10	4	80
20	X09331	1.0	0.82	<5	190	<5	2.21	<1	7	50	782	2.51	<10	0.53	735	45	0.02	3	1100	22	<5	<20	64	0.04	<10	28	<10	3	61
21	X09332	1.0	0.96	<5	350	<5	2.33	1	8	76	758	3.03	<10	0.68	750	27	0.03	5	1130	32	5	<20	122	0.04	<10	44	<10	3	69
22	X09333	0.8	0.90	<5	455	<5	2.37	2	7	62	655	3.11	<10	0.64	715	24	0.03	6	1040	56	10	<20	133	0.04	<10	47	<10	3	66
23	X09334	1.1	0.86	<5	130	<5	2.22	1	8	70	881	2.34	<10	0.61	654	48	0.03	3	1000	26	5	<20	95	0.04	<10	33	<10	3	74
24	X09335	1.3	0.85	<5	230	<5	2.40	2	9	50	1342	2.42	<10	0.62	680	84	0.03	4	1000	24	5	<20	100	0.04	<10	39	<10	3	68
25	X09336	2.0	0.81	<5	105	<5	2.54	1	9	64	1096	2.29	<10	0.53	721	99	0.03	4	970	20	5	<20	56	0.03	<10	31	<10	4	52

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007- 5617 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09337	0.7	0.88	<5	190	<5	2.92	1	8	60	610	2.38	<10	0.64	731	53	0.03	4	1080	16	5	<20	114	0.04	<10	39	<10	4	76
27	X09338	1.3	0.98	<5	310	<5	1.23	<1	8	69	1179	2.00	<10	0.74	515	92	0.04	4	1050	16	5	<20	125	0.04	<10	33	<10	4	58
28	X09339	0.9	0.90	<5	235	<5	1.92	1	8	74	1017	2.04	<10	0.69	537	110	0.04	3	990	18	5	<20	120	0.04	<10	33	<10	3	53
29	X09340	1.0	0.96	<5	310	<5	2.15	<1	8	61	800	2.41	<10	0.72	642	285	0.04	<1	1060	18	<5	<20	118	0.04	<10	42	<10	3	69
30	X09341	0.2	0.58	2135	55	15	0.71	<1	29	24	59	5.01	<10	1.98	817	7	0.13	109	1140	16	20	<20	50	0.05	<10	23	<10	7	58
31	X09342	3.2	0.80	10	115	<5	2.77	3	8	74	2662	2.16	<10	0.54	748	85	0.02	4	810	156	10	<20	73	0.03	<10	24	<10	4	191
32	X09343	1.5	0.86	<5	130	<5	3.53	1	8	64	1079	1.94	<10	0.59	953	74	0.02	3	980	18	5	<20	87	0.03	<10	20	<10	6	53
33	X09344	0.8	0.80	<5	165	<5	2.39	1	8	65	612	2.01	<10	0.53	601	83	0.03	4	980	22	10	<20	93	0.03	<10	26	<10	4	59
34	X09345	1.1	0.81	<5	210	<5	1.53	<1	6	74	862	1.64	<10	0.52	509	70	0.05	4	890	14	<5	<20	109	0.04	<10	25	<10	3	63
35	X09346	1.2	0.94	<5	150	<5	1.85	2	9	49	1072	2.16	<10	0.56	593	66	0.03	2	1000	34	<5	<20	65	0.04	<10	29	<10	4	126
QC DATA:																													
Repeat:																													
1	X09312	1.0	1.40	<5	160	<5	1.96	2	13	59	1174	3.94	<10	1.22	954	58	0.05	6	1360	20	10	<20	112	0.04	<10	74	<10	3	82
10	X09321	2.2	1.03	<5	55	<5	2.15	2	12	50	1354	3.56	<10	0.72	838	60	0.02	5	1070	82	10	<20	90	0.04	<10	34	<10	3	83
19	X09330	1.7	0.83	<5	75	<5	2.94	2	11	65	1489	2.72	<10	0.53	986	51	0.02	5	990	44	10	<20	57	0.03	<10	27	<10	4	82
Resplit:																													
1	X09312	1.1	1.32	<5	110	<5	1.95	3	14	48	1097	4.00	<10	1.18	944	65	0.04	8	1380	22	15	<20	94	0.04	<10	72	<10	3	84
Standard:																													
Pb113A		11.7	0.28	55	45	<5	1.71	37	2	5	2276	1.08	<10	0.12	1522	75	0.02	5	90	5518	20	<20	96	<0.01	10	10	<10	<1	7083

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5617
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5618

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

31-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09347	0.14	0.004
2	X09348	0.61	0.018
3	X09349	0.27	0.008
4	X09350	0.19	0.006
5	X09351	0.23	0.007
6	X09352	0.34	0.010
7	X09353	0.17	0.005
8	X09354	0.16	0.005
9	X09355	0.28	0.008
10	X09356	0.07	0.002
11	X09357	0.22	0.006
12	X09358	0.13	0.004
13	X09359	0.15	0.004
14	X09360	0.16	0.005
15	X09361	0.22	0.006
16	X09362	0.38	0.011
17	X09363	0.24	0.007
18	X09364	0.15	0.004
19	X09365	0.19	0.006
20	X09366	0.21	0.006
21	X09367	<0.03	<0.001
22	X09368	0.35	0.010
23	X09369	0.24	0.007
24	X09370	0.34	0.010
25	X09371	0.29	0.008

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7 - 5718

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X09372	0.15	0.004
27	X09373	0.19	0.006
28	X09374	0.20	0.006
29	X09375	0.16	0.005
30	X09376	0.19	0.006
31	X09377	0.14	0.004
32	X09378	0.18	0.005
33	X09379	0.13	0.004
34	X09380	0.36	0.010
35	X09381	0.21	0.006

QC DATA:

Repeat:

1	X09347	0.17	0.005
10	X09356	0.07	0.002
19	X09365	0.21	0.006

Resplits:

1	X09347	0.17	0.005

Standard:

OXI54		1.89	0.055

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
XLS/07

29-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5618

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09347	2.1	0.80	<5	110	<5	3.31	8	8	60	1941	1.72	<10	0.53	667	326	0.02	2	980	70	<5	<20	119	0.04	<10	20	<10	4	382
2	X09348	2.6	1.14	5	70	<5	1.87	1	12	69	2635	2.32	<10	0.89	769	667	0.03	3	1010	30	10	<20	73	0.04	<10	28	<10	4	135
3	X09349	2.0	0.89	<5	115	<5	2.68	<1	8	86	1311	2.23	<10	0.67	736	187	0.04	4	1080	72	10	<20	70	0.04	<10	33	<10	4	83
4	X09350	3.0	0.78	<5	90	<5	2.41	1	8	104	1331	1.85	<10	0.51	722	85	0.03	4	1020	76	5	<20	50	0.03	<10	22	<10	5	75
5	X09351	1.8	0.88	<5	55	<5	2.87	1	8	71	1075	2.20	<10	0.63	1004	376	0.02	4	1080	50	10	<20	40	0.03	<10	25	<10	5	74
6	X09352	2.9	0.79	<5	50	<5	2.73	2	8	106	2053	2.02	<10	0.59	814	179	0.02	5	900	76	10	<20	49	0.03	<10	21	<10	4	76
7	X09353	0.9	0.92	<5	175	<5	2.95	<1	7	93	718	2.06	<10	0.68	647	687	0.03	4	990	32	10	<20	138	0.04	<10	32	<10	4	59
8	X09354	0.9	0.81	<5	70	<5	3.22	2	8	72	635	2.52	<10	0.57	778	59	0.03	6	1050	18	10	<20	145	0.03	<10	31	<10	3	55
9	X09355	2.3	0.81	<5	70	<5	3.14	1	8	77	1294	1.76	<10	0.58	978	198	0.02	4	960	16	10	<20	51	0.03	<10	21	<10	5	50
10	X09356	0.2	1.01	50	145	<5	0.31	4	63	213	443	>10	<10	0.19	506	121	0.06	437	110	118	10	<20	8	0.06	<10	27	<10	<1	374
11	X09357	2.1	0.78	5	60	<5	5.56	1	12	77	1155	2.09	<10	0.58	1558	37	0.02	5	960	50	10	<20	99	0.03	<10	19	<10	6	48
12	X09358	1.4	0.94	<5	115	<5	2.47	1	8	80	862	1.93	<10	0.70	694	160	0.04	4	1000	16	5	<20	112	0.03	<10	26	<10	3	65
13	X09359	1.0	1.00	<5	125	<5	2.10	2	9	86	818	2.41	<10	0.74	708	83	0.04	5	1120	22	10	<20	79	0.03	<10	34	<10	4	104
14	X09360	1.3	0.89	<5	100	<5	1.99	1	9	69	968	2.27	<10	0.64	705	89	0.03	4	1120	22	<5	<20	68	0.03	<10	28	<10	4	85
15	X09361	2.0	0.83	5	55	<5	4.53	1	9	94	1842	1.99	<10	0.61	1200	384	0.02	4	950	28	5	<20	65	0.03	<10	18	<10	5	61
16	X09362	1.5	0.83	<5	55	<5	3.69	2	9	82	1464	1.94	<10	0.62	836	444	0.03	4	990	20	10	<20	157	0.03	<10	25	<10	4	62
17	X09363	1.5	0.73	5	60	<5	4.03	<1	8	82	1066	1.75	<10	0.51	820	359	0.02	3	970	16	5	<20	164	0.03	<10	22	<10	4	49
18	X09364	1.0	0.76	<5	100	<5	4.53	<1	8	88	664	1.97	<10	0.52	934	70	0.03	<1	940	16	<5	<20	189	0.03	<10	25	<10	3	54
19	X09365	1.0	0.79	<5	195	<5	3.37	2	8	79	999	2.00	<10	0.56	792	261	0.03	6	1040	22	10	<20	144	0.03	<10	32	<10	3	54
20	X09366	1.6	0.84	10	50	<5	2.34	<1	9	77	1182	2.11	<10	0.68	731	327	0.03	4	1060	22	<5	<20	94	0.03	<10	26	<10	5	62
21	X09367	<0.2	1.04	<5	250	10	0.59	<1	6	97	6	2.05	<10	0.59	531	6	0.11	7	870	12	10	<20	96	0.05	<10	45	<10	<1	41
22	X09368	1.9	0.78	5	75	<5	2.69	<1	8	76	1468	1.66	<10	0.60	680	711	0.03	2	1040	20	<5	<20	115	0.03	<10	22	<10	6	38
23	X09369	2.0	0.85	10	25	<5	3.62	1	10	86	1343	1.94	<10	0.65	1299	162	0.03	4	1130	32	10	<20	95	0.03	<10	22	<10	7	48
24	X09370	2.5	0.79	<5	85	<5	2.01	1	8	106	1426	2.22	<10	0.58	709	207	0.03	4	900	260	5	<20	91	0.03	<10	30	<10	5	64
25	X09371	2.2	0.79	<5	40	<5	3.74	1	11	82	1088	2.80	<10	0.58	1027	208	0.03	4	860	24	5	<20	126	0.03	<10	30	<10	4	54

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09372	1.6	0.68	<5	60	<5	2.29	1	8	77	886	2.06	<10	0.49	610	354	0.03	4	950	20	10	<20	155	0.03	<10	36	<10	3	51
27	X09373	1.8	0.65	<5	100	<5	2.84	<1	7	95	856	1.65	<10	0.41	786	81	0.02	4	940	12	<5	<20	167	0.03	<10	22	<10	4	37
28	X09374	5.6	0.31	<5	15	<5	4.63	2	7	95	886	3.03	<10	0.16	1552	182	0.01	5	660	54	<5	<20	377	0.03	<10	12	<10	2	56
29	X09375	2.4	0.68	5	50	<5	2.72	12	8	84	921	1.82	<10	0.49	924	133	0.02	5	1030	164	15	<20	138	0.02	<10	20	<10	6	661
30	X09376	1.6	0.69	<5	65	<5	2.37	3	6	93	1069	1.43	<10	0.48	560	216	0.02	4	960	62	<5	<20	120	0.03	<10	18	<10	5	157
31	X09377	1.5	0.68	5	35	<5	3.11	1	8	90	1183	1.74	<10	0.56	408	143	0.03	4	720	32	<5	<20	254	0.03	<10	21	<10	3	59
32	X09378	1.4	1.01	<5	70	<5	2.63	1	10	88	1130	2.24	<10	0.83	633	82	0.04	5	1050	14	10	<20	184	0.04	<10	34	<10	3	72
33	X09379	2.3	1.03	<5	65	<5	1.70	1	9	88	1809	2.02	<10	0.85	527	97	0.05	5	1050	16	10	<20	192	0.04	<10	32	<10	3	72
34	X09380	2.4	1.05	<5	50	<5	2.22	2	10	95	2108	2.23	<10	0.85	584	77	0.04	5	1100	16	10	<20	173	0.04	<10	36	<10	4	70
35	X09381	1.8	1.05	<5	70	<5	1.74	2	11	81	1345	2.31	<10	0.86	524	106	0.04	5	1160	16	15	<20	161	0.04	<10	39	<10	4	68
QC DATA:																													
Repeat:																													
1	X09347	2.1	0.83	<5	115	<5	3.35	7	8	62	2000	1.74	<10	0.54	676	319	0.02	<1	990	68	<5	<20	128	0.04	<10	21	<10	4	379
19	X09365	1.0	0.80	<5	165	<5	3.44	2	8	79	1020	2.02	<10	0.57	808	248	0.03	3	1060	22	<5	<20	146	0.03	<10	33	<10	3	54
Resplit:																													
1	X09347	2.3	0.86	5	95	<5	3.49	22	9	64	2060	1.84	<10	0.58	664	373	0.02	2	900	86	5	<20	135	0.05	<10	21	<10	6	374
Standard:																													
Pb113A		10.7	0.26	50	50	<5	1.78	38	2	5	2310	1.05	<10	0.12	1448	75	0.02	2	70	5402	20	<20	91	<0.01	<10	8	<10	<1	6952

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
dl/5617
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5621

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07135
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	G35838	14.4	0.420	77.2	2.251
2	G35839	1.31	0.038		
3	G35840	1.02	0.030		
4	G35841	1.06	0.031		
5	G35842	0.64	0.019		
6	G35843	0.85	0.025		
7	G35844	1.07	0.031		
8	G35845	0.73	0.021		
9	G35846	0.76	0.022		
10	G35847	0.60	0.017		
11	G35848	0.92	0.027		
12	G35849	0.68	0.020		
13	G35850	0.63	0.018		
14	G35851	0.87	0.025		
15	G35852	1.07	0.031		
16	G35853	1.16	0.034		
17	G35854	0.82	0.024		
18	G35855	0.67	0.020		
19	G35856	0.62	0.018		
20	G35857	0.63	0.018		
21	G35858	0.81	0.024		
22	G35859	0.57	0.017		
23	G35860	0.63	0.018		
24	G35861	0.52	0.015		
25	G35862	0.76	0.022		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AK7-5621 30-Oct-07

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
26	G35863	0.81	0.024		
27	G35864	0.61	0.018		
28	G35865	0.58	0.017		
29	G35866	0.60	0.017		
30	G35867	0.66	0.019		
31	G35868	0.81	0.024		
32	G35869	0.58	0.017		
33	G35870	0.60	0.017		
34	G35871	1.81	0.053		
35	G35872	<0.03	<0.001		
QC DATA:					
Repeat:					
1	G35838	14.6	0.426	76.9	2.243
2	G35839	1.42	0.041		
7	G35844	1.12	0.033		
10	G35847	0.64	0.019		
16	G35853	1.13	0.033		
19	G35856	0.63	0.018		
Resplits:					
1	G35838	15.0	0.437		
Standard:					
OXi54		1.87	0.055		
PB113				21.8	0.636

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
XLS/07

29-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5621

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07135
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35838	>30	0.51	245	50	<5	0.66	5	19	110	1818	4.84	<10	0.18	271	45	0.02	8	1390	76	230	<20	33	0.02	<10	15	<10	3	79
2	G35839	18.0	0.95	10	55	<5	1.88	2	14	122	3226	4.42	10	0.76	732	51	0.02	8	960	32	10	<20	135	0.01	<10	34	<10	3	36
3	G35840	5.7	1.22	<5	60	<5	1.70	1	11	91	2607	4.26	10	1.03	542	111	0.02	5	1010	18	5	<20	124	0.01	<10	37	<10	3	31
4	G35841	5.3	1.34	25	70	<5	1.45	4	14	126	2442	6.48	20	1.19	691	58	0.02	13	1100	24	25	<20	104	0.01	<10	38	<10	2	36
5	G35842	3.3	1.40	20	55	<5	1.60	1	19	118	1777	4.54	10	1.33	754	82	0.02	7	1270	20	10	<20	113	0.02	<10	41	<10	3	39
6	G35843	4.2	1.16	10	65	<5	1.87	1	17	127	2604	4.81	10	1.02	662	62	0.02	7	1080	22	5	<20	130	0.02	<10	38	<10	4	30
7	G35844	2.1	1.40	30	80	<5	2.29	1	14	96	1353	3.70	10	1.19	585	64	0.02	7	1320	18	5	<20	176	0.02	<10	43	<10	5	29
8	G35845	2.3	0.97	5	60	<5	2.51	<1	15	103	1735	3.99	<10	0.82	641	62	0.02	6	1260	18	<5	<20	168	0.02	<10	34	<10	4	22
9	G35846	4.9	1.30	<5	65	<5	1.86	1	19	109	2208	5.64	10	1.22	742	54	0.02	8	1120	32	5	<20	140	0.02	<10	41	<10	2	30
10	G35847	7.9	1.28	15	60	<5	1.41	<1	19	133	2057	4.90	10	1.25	666	73	0.02	7	1120	28	<5	<20	100	0.02	<10	43	<10	2	34
11	G35848	13.4	1.45	<5	60	<5	1.40	1	21	133	2455	5.70	10	1.45	775	72	0.02	9	1240	782	5	<20	90	0.02	<10	51	<10	3	58
12	G35849	4.1	1.37	10	60	<5	1.61	<1	13	108	1601	4.85	10	1.31	565	52	0.03	7	1180	24	<5	<20	105	0.02	<10	52	<10	3	34
13	G35850	1.5	1.62	<5	65	<5	2.19	2	14	94	1309	4.46	10	1.37	540	103	0.03	7	1220	24	10	<20	169	0.02	<10	70	<10	4	30
14	G35851	2.5	1.35	<5	60	<5	2.00	1	15	93	2031	4.48	10	1.12	456	96	0.03	7	1250	22	5	<20	147	0.02	<10	56	<10	4	29
15	G35852	3.3	1.19	<5	60	<5	1.58	1	14	135	2545	4.16	10	1.02	391	100	0.03	8	890	20	10	<20	128	<0.01	<10	51	<10	3	28
16	G35853	2.7	1.17	<5	60	<5	1.63	<1	15	136	2076	4.08	<10	0.97	403	72	0.03	7	940	20	<5	<20	135	0.01	<10	50	<10	3	24
17	G35854	2.0	1.69	<5	85	<5	2.12	<1	14	147	2001	4.46	10	1.40	466	80	0.04	7	1110	22	<5	<20	211	0.02	<10	63	<10	4	32
18	G35855	2.1	1.70	<5	75	<5	2.03	<1	13	104	1770	5.19	10	1.53	559	57	0.03	4	1240	26	<5	<20	186	0.02	<10	79	<10	4	34
19	G35856	4.1	1.16	<5	65	<5	0.94	2	16	137	1679	5.67	10	1.15	573	102	0.02	5	1060	52	<5	<20	76	0.02	<10	49	<10	<1	59
20	G35857	2.7	1.53	1650	<5	<5	1.42	<1	36	120	1839	4.34	30	1.24	584	69	<0.01	<1	770	<2	<5	<20	<1	0.02	<10	243	<10	16	26
21	G35858	2.8	1.27	10	60	<5	0.78	<1	13	149	1461	3.63	<10	1.20	371	93	0.03	5	1310	30	<5	<20	64	0.01	<10	52	<10	3	43
22	G35859	2.8	1.28	10	65	<5	0.98	4	17	125	1799	5.55	10	1.37	628	82	0.02	14	1210	44	35	<20	77	<0.01	<10	60	<10	2	71
23	G35860	5.1	1.50	550	<5	50	1.04	<1	27	136	2083	5.95	40	1.63	682	95	0.03	28	1100	92	85	<20	59	<0.01	<10	136	<10	32	66
24	G35861	3.9	1.69	5	75	<5	1.30	1	12	114	944	4.72	10	1.57	552	62	0.04	7	1350	34	10	<20	97	0.02	<10	78	<10	4	58
25	G35862	5.5	1.52	10	75	<5	1.69	<1	19	115	2590	4.84	10	1.40	615	104	0.03	8	1240	44	10	<20	143	0.01	<10	70	<10	5	34

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35863	2.0	1.59	10	85	<5	1.07	2	15	103	1682	4.94	10	1.47	369	91	0.04	10	1250	30	20	<20	100	0.01	<10	88	<10	4	30
27	G35864	1.9	1.50	<5	105	<5	1.50	<1	12	99	1515	4.15	10	1.36	384	84	0.04	6	1270	26	<5	<20	154	0.02	<10	84	<10	4	31
28	G35865	1.3	1.71	20	90	<5	1.68	<1	15	94	1092	4.87	10	1.59	394	65	0.04	6	1560	28	<5	<20	142	0.02	<10	93	<10	5	32
29	G35866	2.1	1.64	<5	90	<5	1.85	1	14	105	1565	5.18	10	1.50	450	100	0.05	8	1410	28	5	<20	173	0.02	<10	95	<10	4	31
30	G35867	2.9	1.61	15	65	<5	1.49	3	15	110	1659	4.82	10	1.45	573	71	0.02	8	1440	36	10	<20	118	0.02	<10	59	<10	4	99
31	G35868	2.5	1.20	15	70	<5	1.54	2	18	121	1909	4.82	10	1.06	516	73	0.03	6	1250	30	<5	<20	165	0.02	<10	53	<10	3	45
32	G35869	1.8	1.48	25	65	<5	2.48	<1	13	107	1411	4.01	10	1.38	728	83	0.04	7	1320	26	5	<20	230	0.02	<10	62	<10	5	36
33	G35870	1.7	1.33	10	60	<5	2.26	1	17	98	1054	4.45	10	1.24	734	77	0.03	6	1520	30	<5	<20	198	0.03	<10	49	<10	4	49
34	G35871	4.1	1.16	30	50	<5	1.06	2	23	56	8572	4.11	20	0.66	212	568	0.04	62	150	68	20	<20	53	0.04	<10	45	<10	7	73
35	G35872	<0.2	1.10	15	265	<5	0.60	<1	7	100	5	2.22	10	0.62	550	4	0.12	5	990	20	<5	<20	80	0.13	<10	48	<10	7	43
QC DATA:																													
Repeat:																													
1	G35838	>30	0.51	225	50	<5	0.67	6	18	108	1819	4.69	10	0.19	276	52	0.02	8	1400	74	225	<20	32	0.01	<10	15	<10	3	74
10	G35847	7.7	1.37	20	65	<5	1.35	<1	15	141	1983	4.75	10	1.36	683	65	0.02	3	1120	30	<5	<20	111	0.03	<10	50	<10	3	41
19	G35856	3.9	1.22	<5	55	<5	1.10	1	17	108	1596	5.34	<10	1.17	537	60	0.02	7	1120	40	5	<20	90	0.01	<10	48	<10	3	57
Resplit:																													
1	G35838	>30	0.47	250	55	<5	0.73	7	18	90	1752	4.81	10	0.18	354	59	0.01	9	1530	92	285	<20	39	0.01	<10	14	<10	3	89
Standard:																													
Pb113A		10.9	0.29	45	65	<5	1.76	40	2	5	2199	1.10	<10	0.13	1498	74	0.02	3	80	5402	20	<20	91	<0.01	<10	9	<10	<1	6915

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5617
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5622

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Oct-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07135
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	G35873	0.56	0.016		
2	G35874	0.60	0.017		
3	G35875	0.61	0.018		
4	G35876	0.60	0.017		
5	G35877	0.47	0.014		
6	G35878	0.60	0.017		
7	G35879	0.53	0.015		
8	G35880	0.60	0.017		
9	G35881	0.87	0.025	42.6	1.242
10	G35882	0.59	0.017		
11	G35883	0.52	0.015		
12	G35884	0.69	0.020		
13	G35885	0.50	0.015		
14	G35886	1.02	0.030		
15	G35887	0.45	0.013		
16	G35888	0.45	0.013		
17	G35889	0.33	0.010		
18	G35890	0.37	0.011		
19	G35891	0.29	0.008		
20	G35892	0.36	0.010		
21	G35893	0.40	0.012		
22	G35894	0.30	0.009		
23	G35895	0.52	0.015		
24	G35896	<0.03	<0.001		
25	G35897	0.30	0.009		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AK7-5622 30-Oct-07

ET #	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
26	G35898	0.28	0.008		
27	G35899	0.41	0.012		
28	G35900	0.33	0.010		
29	G35901	0.42	0.012		
30	G35902	0.33	0.010		
31	G35903	0.28	0.008		
32	G35904	0.28	0.008	90.3	2.633
33	G35905	0.55	0.016		
34	G35906	0.25	0.007		
35	G35907	0.34	0.010		
QC DATA:					
Repeat:					
1	G35873	0.58	0.017		
9	G35881			43.9	1.280
10	G35882	0.59	0.017		
19	G35891	0.25	0.007		
Resplits:					
1	G35873	0.61	0.018		
Standard:					
OXi54		1.83	0.053		
PB113				21.6	0.630

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

29-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5622

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07135
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35873	2.0	1.53	<5	65	<5	1.37	3	17	86	1534	5.36	10	1.47	648	58	0.04	8	1190	22	10	<20	109	0.02	<10	74	<10	3	48
2	G35874	2.0	1.13	<5	55	<5	1.05	1	10	79	1716	3.53	<10	1.02	451	133	0.03	6	1040	22	5	<20	119	0.01	<10	52	<10	4	28
3	G35875	2.0	1.48	<5	50	<5	1.21	1	13	100	1528	4.54	10	1.37	497	78	0.03	6	1250	24	5	<20	128	0.02	<10	67	<10	3	33
4	G35876	3.1	1.47	10	60	<5	1.34	1	15	91	1893	4.13	10	1.44	601	162	0.03	6	1260	24	10	<20	137	0.02	<10	65	<10	4	35
5	G35877	2.7	1.46	10	55	<5	1.39	1	15	84	1381	4.22	10	1.36	665	132	0.03	6	1340	26	5	<20	137	0.02	<10	57	<10	4	37
6	G35878	3.2	1.46	<5	60	<5	1.80	2	16	104	1987	5.33	10	1.26	642	130	0.03	7	1060	24	<5	<20	169	0.02	<10	65	<10	3	32
7	G35879	3.5	1.33	15	55	<5	1.30	1	16	98	1381	4.96	10	1.26	741	102	0.02	7	1390	26	10	<20	106	0.02	<10	42	<10	3	36
8	G35880	8.7	0.79	45	50	<5	1.13	2	14	108	1191	4.29	<10	0.59	553	137	0.02	7	1060	28	10	<20	75	0.02	<10	24	<10	3	30
9	G35881	>30	0.61	150	45	<5	0.57	6	14	118	1552	4.06	<10	0.38	275	106	0.02	3	740	682	80	<20	56	0.01	<10	15	<10	1	110
10	G35882	3.2	0.74	25	65	<5	1.52	1	9	93	1034	2.93	<10	0.46	580	80	0.02	4	860	20	<5	<20	120	0.01	<10	19	<10	5	24
11	G35883	4.0	0.93	<5	55	<5	1.60	2	13	92	1082	3.27	10	0.59	489	56	0.03	5	850	24	15	<20	136	<0.01	<10	23	<10	5	51
12	G35884	3.4	0.86	<5	50	<5	1.59	1	12	100	1814	3.22	<10	0.61	435	154	0.03	5	810	22	5	<20	135	0.01	<10	22	<10	5	31
13	G35885	2.8	0.63	15	45	<5	1.46	1	11	109	1879	2.47	<10	0.36	326	173	0.02	3	730	30	<5	<20	110	0.01	<10	16	<10	3	25
14	G35886	3.7	1.30	50	80	<5	0.78	4	18	59	3293	4.02	30	0.57	278	215	0.04	13	360	132	30	<20	32	0.03	<10	48	<10	7	154
15	G35887	2.1	0.85	<5	60	<5	1.20	2	10	101	1561	2.63	<10	0.64	308	78	0.04	3	680	20	<5	<20	87	<0.01	<10	23	<10	3	38
16	G35888	1.6	0.92	<5	55	<5	1.77	<1	12	103	1373	2.97	10	0.69	370	205	0.04	3	710	22	<5	<20	124	0.01	<10	28	<10	5	21
17	G35889	2.7	0.85	<5	50	<5	1.78	1	12	80	1027	3.33	<10	0.60	398	65	0.03	4	950	22	<5	<20	149	0.01	<10	23	<10	5	19
18	G35890	5.7	0.61	<5	50	<5	1.79	<1	15	90	1360	3.25	<10	0.38	503	123	0.02	3	820	22	<5	<20	119	0.01	<10	16	<10	4	16
19	G35891	4.6	0.91	<5	75	<5	1.91	<1	10	90	951	2.47	<10	0.59	560	54	0.02	4	1010	24	5	<20	118	0.01	<10	20	<10	6	25
20	G35892	5.6	0.84	10	60	<5	1.47	1	11	96	712	3.03	<10	0.48	511	45	0.02	4	1050	28	5	<20	90	0.01	<10	23	<10	5	23
21	G35893	5.6	0.97	<5	60	<5	2.07	1	15	154	1228	3.76	10	0.78	650	123	0.02	6	1020	24	<5	<20	156	0.02	<10	37	<10	4	26
22	G35894	3.0	1.52	<5	65	<5	1.70	2	17	89	1144	4.51	10	1.28	533	178	0.04	8	1290	26	10	<20	127	0.02	<10	71	<10	5	33
23	G35895	3.5	1.38	15	70	<5	1.72	<1	14	127	1412	3.56	10	1.22	497	80	0.04	7	1240	22	<5	<20	148	0.02	<10	67	<10	6	34
24	G35896	<0.2	1.24	<5	265	10	0.61	<1	8	90	6	2.39	10	0.68	596	3	0.13	6	950	18	<5	<20	93	0.15	<10	52	<10	8	40
25	G35897	2.3	1.48	<5	60	<5	1.55	1	15	111	777	4.33	10	1.32	457	139	0.04	7	1480	32	<5	<20	125	0.02	<10	66	<10	6	39

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007-5622 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35898	10.9	0.97	10	50	<5	1.92	2	17	94	1514	4.14	<10	0.81	559	242	0.02	6	1170	70	15	<20	162	0.01	<10	34	<10	5	78
27	G35899	3.8	1.18	<5	60	<5	1.93	1	13	82	1296	3.21	<10	1.04	584	84	0.02	5	1350	22	10	<20	150	0.01	<10	42	<10	6	28
28	G35900	2.0	1.19	5	65	<5	2.31	<1	15	92	990	3.36	<10	1.01	703	132	0.03	5	1300	24	5	<20	192	0.02	<10	37	<10	6	27
29	G35901	2.6	1.02	10	55	<5	1.74	<1	15	118	1174	3.33	<10	0.83	548	225	0.02	4	1250	22	<5	<20	144	0.01	<10	37	<10	5	27
30	G35902	2.5	1.13	<5	55	<5	1.61	1	15	75	958	3.98	10	0.95	594	155	0.03	5	1340	32	10	<20	125	0.02	<10	42	<10	5	37
31	G35903	5.5	1.34	20	55	<5	1.38	2	16	86	1001	4.27	10	1.17	418	109	0.03	5	1380	42	10	<20	126	0.02	<10	52	<10	4	50
32	G35904	>30	0.33	165	50	<5	0.72	9	12	119	2129	3.48	<10	0.04	225	230	0.01	5	650	594	225	<20	80	<0.01	<10	8	<10	1	266
33	G35905	10.5	0.78	5	40	<5	0.66	2	15	95	837	3.74	<10	0.62	329	133	0.02	7	1330	90	15	<20	57	<0.01	<10	28	<10	4	33
34	G35906	4.5	1.24	<5	50	<5	0.72	<1	17	88	1007	3.73	10	1.21	459	81	0.02	6	1480	26	<5	<20	71	0.01	<10	46	<10	4	42
35	G35907	4.2	1.29	<5	60	<5	0.87	<1	13	106	1093	3.54	<10	1.32	493	115	0.02	4	1460	34	5	<20	82	0.01	<10	39	<10	4	46
QC DATA:																													
Repeat:																													
1	G35873	2.2	1.48	<5	60	<5	1.38	2	17	80	1539	5.39	10	1.47	652	61	0.03	7	1180	22	5	<20	109	0.02	<10	70	<10	3	48
10	G35882	3.3	0.63	20	60	<5	1.50	1	9	86	1018	2.88	<10	0.43	573	67	0.02	4	850	20	<5	<20	115	0.01	<10	17	<10	5	24
19	G35891	4.5	0.81	<5	65	<5	1.91	<1	10	82	953	2.44	<10	0.58	559	44	0.02	3	990	20	<5	<20	122	0.01	<10	18	<10	6	24
Resplit:																													
1	G35873	2.1	1.56	<5	60	<5	1.51	2	16	77	1559	5.01	10	1.51	673	85	0.04	8	1210	24	5	<20	121	0.02	<10	72	<10	3	50
Standard:																													
Pb113A		11.2	0.32	40	60	<5	1.69	37	2	<1	2224	1.01	<10	0.11	1446	69	0.02	1	90	5488	10	<20	81	0.01	<10	4	<10	1	6998

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5622
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5623

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Oct-07

No. of samples received: 30
Sample Type: Core
Project: KSM
Shipment #: 07137
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09382	0.11	0.003
2	X09383	0.31	0.009
3	X09384	0.22	0.006
4	X09385	0.28	0.008
5	X09386	0.32	0.009
6	X09387	0.10	0.003
7	X09388	0.24	0.007
8	X09389	0.27	0.008
9	X09390	0.25	0.007
10	X09391	0.27	0.008
11	X09392	0.39	0.011
12	X09393	0.33	0.010
13	X09394	0.07	0.002
14	X09395	0.39	0.011
15	X09396	0.34	0.010
16	X09397	0.11	0.003
17	X09398	0.09	0.003
18	X09399	0.12	0.003
19	X09400	0.15	0.004
20	X09401	0.42	0.012
21	X09402	0.14	0.004
22	X09403	0.41	0.012
23	X09404	0.17	0.005
24	X09405	0.06	0.002
25	X09406	<0.03	<0.001

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AK7-5623 30-Oct-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X09407	0.10	0.003
27	X09408	0.11	0.003
28	X09409	0.18	0.005
29	X09410	0.17	0.005
30	X09411	0.13	0.004

QC DATA:

Repeat:

1	X09382	0.11	0.003
10	X09391	0.31	0.009
19	X09400	0.15	0.004
30	X09411	0.12	0.003

Resplits:

1	X09382	0.15	0.004

Standard:

OXi54		1.88	0.055

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

29-Oct-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5623

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 30
Sample Type: Core
Project: KSM
Shipment #: 07137
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09382	1.2	1.14	10	70	<5	2.62	<1	11	96	996	2.37	10	0.88	585	100	0.04	2	1150	24	10	<20	248	0.10	<10	42	<10	7	68
2	X09383	1.0	1.20	10	70	<5	1.97	<1	14	101	819	2.33	10	0.87	522	218	0.05	3	1170	28	10	<20	252	0.11	<10	38	<10	7	69
3	X09384	0.9	1.55	15	65	<5	1.99	<1	14	95	634	2.95	10	1.28	738	51	0.04	4	1130	26	10	<20	235	0.11	<10	42	<10	6	102
4	X09385	1.8	0.86	15	35	<5	3.82	<1	13	97	1688	1.69	<10	0.72	334	268	0.04	3	1030	22	<5	<20	348	0.12	<10	41	<10	11	45
5	X09386	1.3	1.03	<5	55	<5	2.84	<1	14	84	1094	2.30	10	0.80	486	367	0.04	3	1130	24	5	<20	234	0.12	<10	44	<10	9	61
6	X09387	1.2	1.04	10	90	<5	1.89	<1	10	135	859	2.47	10	0.76	495	496	0.04	4	960	18	5	<20	184	0.11	<10	42	<10	8	63
7	X09388	1.7	1.18	5	70	<5	2.17	1	12	91	1290	2.79	10	0.84	609	114	0.04	3	1210	38	5	<20	178	0.13	<10	43	<10	9	82
8	X09389	2.2	0.76	10	50	<5	5.43	1	9	141	1335	1.67	<10	0.54	734	190	0.02	5	760	42	15	<20	312	0.07	<10	25	<10	8	48
9	X09390	2.0	0.69	20	45	<5	4.28	<1	9	106	1559	1.42	<10	0.47	575	866	0.03	<1	810	42	<5	<20	221	0.08	<10	26	<10	10	28
10	X09391	2.0	0.91	15	50	<5	3.42	<1	11	87	1448	2.23	10	0.72	612	444	0.03	2	1080	16	10	<20	231	0.08	<10	33	<10	9	47
11	X09392	2.4	0.90	10	65	<5	4.09	<1	12	76	1609	2.04	10	0.59	779	181	0.02	3	1190	16	5	<20	168	0.09	<10	25	<10	9	53
12	X09393	3.1	0.81	15	50	<5	3.66	<1	12	94	2026	1.78	<10	0.57	529	237	0.02	<1	970	20	<5	<20	244	0.09	<10	30	<10	10	38
13	X09394	0.3	0.91	5	115	5	0.33	6	85	260	458	>10	10	0.21	483	129	0.06	476	130	110	<5	<20	11	0.05	<10	30	<10	<1	384
14	X09395	2.6	0.92	10	55	<5	3.32	<1	10	83	1450	2.13	10	0.77	419	616	0.04	3	970	22	<5	<20	261	0.13	<10	57	<10	11	42
15	X09396	9.1	0.81	<5	105	<5	2.61	1	11	103	1234	3.20	10	0.55	483	173	0.05	4	1290	20	<5	<20	189	0.12	<10	72	<10	8	55
16	X09397	1.5	0.79	<5	50	<5	3.86	<1	34	95	555	4.04	10	0.43	716	156	0.02	3	1100	24	<5	<20	167	0.09	<10	25	<10	6	35
17	X09398	1.1	0.84	10	60	<5	3.97	<1	11	80	570	2.05	10	0.48	648	278	0.03	2	1210	16	5	<20	238	0.11	<10	33	<10	9	33
18	X09399	1.2	0.87	5	85	<5	3.16	<1	13	83	546	2.39	10	0.48	590	49	0.03	2	1300	20	<5	<20	166	0.11	<10	39	<10	8	39
19	X09400	1.5	0.71	<5	45	<5	4.78	1	10	63	679	1.84	<10	0.43	691	66	0.02	2	1160	28	<5	<20	260	0.08	<10	18	<10	7	49
20	X09401	2.3	0.77	20	55	<5	4.11	<1	15	67	1363	2.39	10	0.49	625	146	0.02	3	1160	20	<5	<20	198	0.08	<10	26	<10	7	36
21	X09402	1.0	1.03	10	80	<5	2.33	<1	13	86	638	2.68	10	0.81	538	78	0.04	2	1260	18	<5	<20	181	0.11	<10	53	<10	7	44
22	X09403	1.2	0.84	10	60	<5	2.51	<1	11	104	916	1.96	10	0.64	371	114	0.04	3	1140	20	<5	<20	166	0.11	<10	46	<10	9	36
23	X09404	0.9	0.89	10	90	<5	2.60	<1	12	103	847	2.36	10	0.54	354	47	0.05	4	1450	18	<5	<20	195	0.13	<10	61	<10	9	34
24	X09405	0.8	1.14	15	65	<5	3.87	<1	11	88	492	2.47	10	0.83	634	33	0.04	3	1270	24	10	<20	246	0.11	<10	47	<10	7	46
25	X09406	<0.2	1.21	10	270	25	0.71	<1	8	100	5	2.48	10	0.61	604	4	0.12	6	940	24	5	<20	98	0.18	<10	52	<10	8	44

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09407	0.8	1.18	15	95	<5	2.40	<1	13	89	503	2.58	10	0.82	526	58	0.04	3	1360	24	5	<20	184	0.13	<10	51	<10	9	46
27	X09408	1.2	1.14	10	70	<5	3.16	<1	13	71	708	2.40	10	0.80	486	71	0.04	3	1330	24	5	<20	223	0.15	<10	57	<10	9	43
28	X09409	1.0	1.09	10	70	<5	2.69	<1	12	87	805	2.62	10	0.79	539	48	0.04	4	1370	24	<5	<20	169	0.10	<10	42	<10	6	41
29	X09410	1.1	0.99	15	65	<5	2.54	<1	12	73	830	2.45	10	0.71	667	79	0.02	4	1340	38	10	<20	77	0.06	<10	26	<10	6	41
30	X09411	0.9	0.81	20	65	<5	3.81	<1	10	60	523	2.13	<10	0.52	738	33	0.02	2	1310	16	<5	<20	117	0.07	<10	24	<10	6	32
QC DATA:																													
Repeat:																													
1	X09382	1.1	1.31	5	90	<5	2.85	<1	12	110	1007	2.51	10	0.90	609	101	0.04	3	1190	28	5	<20	274	0.14	<10	52	<10	9	70
10	X09391	2.1	1.06	20	60	<5	3.59	<1	12	97	1471	2.32	10	0.76	628	466	0.03	4	1100	22	15	<20	258	0.10	<10	40	<10	11	48
19	X09400	1.4	0.85	20	50	<5	4.92	1	11	72	681	1.95	<10	0.45	714	62	0.02	2	1200	36	<5	<20	278	0.12	<10	23	<10	10	52
Resplit:																													
1	X09382	1.3	1.28	10	70	<5	3.00	<1	14	113	1022	2.70	10	0.93	661	87	0.04	4	1210	30	5	<20	263	0.12	<10	48	<10	7	78
Standard:																													
Pb113A		10.9	0.24	40	70	<5	1.68	42	3	6	2338	1.17	<10	0.11	1574	72	0.02	1	70	5404	15	<20	95	0.02	<10	9	<10	<1	6950

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

JJ/jl
df/5622
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5626

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

7-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07138
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09412	1.01	0.029
2	X09413	1.18	0.034
3	X09414	0.58	0.017
4	X09415	0.54	0.016
5	X09416	0.50	0.015
6	X09417	0.63	0.018
7	X09418	0.84	0.024
8	X09419	0.74	0.022
9	X09420	0.70	0.020
10	X09421	1.16	0.034
11	X09422	0.97	0.028
12	X09423	1.03	0.030
13	X09424	1.25	0.036
14	X09425	1.39	0.041
15	X09426	1.23	0.036
16	X09427	0.79	0.023
17	X09428	0.75	0.022
18	X09429	0.74	0.022
19	X09430	0.35	0.010
20	X09431	<0.03	<0.001
21	X09432	1.07	0.031
22	X09433	0.80	0.023
23	X09434	1.21	0.035
24	X09435	1.02	0.030
25	X09436	0.28	0.008

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AK7-5626 7-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X09437	0.88	0.026
27	X09438	0.82	0.024
28	X09439	1.25	0.036
29	X09440	1.08	0.031
30	X09441	1.11	0.032
31	X09442	1.05	0.031
32	X09443	0.99	0.029
33	X09444	0.74	0.022
34	X09445	1.32	0.038
35	X09446	1.17	0.034

QC DATA:

Repeat:

1	X09412	0.97	0.028
10	X09421	1.17	0.034
14	X09425	1.30	0.038
19	X09430	0.40	0.012
28	X09439	1.22	0.036
32	X09443	1.07	0.031
34	X09445	1.28	0.037
35	X09446	1.14	0.033

Resplits:

1	X09412	0.99	0.029

Standard:

OXi54		1.86	0.054

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

9-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5626

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07138
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09412	1.6	0.78	20	70	<5	0.24	2	11	85	2047	4.23	<10	0.37	198	20	<0.01	5	980	38	10	<20	19	0.02	<10	11	<10	4	99
2	X09413	2.5	0.29	10	50	<5	0.17	4	14	105	4865	5.25	<10	0.01	47	14	<0.01	8	550	32	5	<20	11	<0.01	<10	6	<10	<1	58
3	X09414	2.4	0.21	30	45	<5	0.09	2	10	176	4000	4.40	<10	<0.01	34	10	<0.01	8	190	30	10	<20	10	<0.01	<10	7	<10	<1	33
4	X09415	3.5	0.22	175	50	<5	0.17	5	12	173	3046	5.16	<10	<0.01	34	15	<0.01	8	570	26	25	<20	12	<0.01	<10	6	<10	<1	70
5	X09416	2.8	0.33	355	70	<5	0.21	7	14	131	4387	5.97	<10	<0.01	61	12	0.01	7	550	32	20	<20	16	<0.01	<10	7	<10	<1	123
6	X09417	1.7	0.25	15	45	<5	0.25	2	12	143	3928	4.23	<10	0.03	90	14	<0.01	6	620	24	<5	<20	22	<0.01	<10	5	<10	<1	23
7	X09418	3.4	0.27	<5	50	<5	0.53	2	10	161	4492	3.97	<10	0.12	342	11	<0.01	6	300	40	<5	<20	33	<0.01	<10	5	<10	<1	48
8	X09419	1.8	0.25	<5	50	<5	0.22	3	13	139	2539	5.17	<10	<0.01	44	17	<0.01	7	790	38	<5	<20	14	<0.01	<10	6	<10	<1	62
9	X09420	2.0	0.30	<5	55	<5	0.18	2	12	131	2947	4.63	<10	<0.01	41	12	<0.01	5	580	40	<5	<20	15	<0.01	<10	7	<10	<1	44
10	X09421	2.0	0.30	<5	55	<5	0.19	3	15	163	3833	5.23	<10	<0.01	50	19	0.01	8	560	36	<5	<20	10	<0.01	<10	6	<10	<1	52
11	X09422	1.4	0.63	<5	50	<5	0.18	3	10	124	3155	5.01	<10	0.20	198	17	<0.01	9	630	32	15	<20	14	<0.01	<10	10	<10	<1	106
12	X09423	1.8	0.24	<5	60	<5	0.14	3	14	169	5003	5.08	<10	<0.01	75	15	<0.01	6	210	36	<5	<20	27	<0.01	<10	5	<10	<1	53
13	X09424	1.6	0.24	<5	45	<5	0.22	2	10	151	4658	4.78	<10	0.02	136	12	<0.01	6	330	34	<5	<20	19	<0.01	<10	5	<10	<1	48
14	X09425	1.3	1.10	<5	105	<5	0.92	2	10	155	3106	4.09	<10	0.53	563	16	0.01	8	690	36	15	<20	48	0.01	<10	17	<10	1	79
15	X09426	1.0	0.59	<5	55	<5	1.12	2	12	169	3216	4.75	<10	0.36	533	14	0.01	7	640	62	<5	<20	60	<0.01	<10	11	<10	<1	82
16	X09427	1.1	1.19	<5	75	<5	0.89	2	12	117	2794	5.35	<10	0.69	383	19	<0.01	7	860	48	10	<20	49	<0.01	<10	24	<10	<1	59
17	X09428	0.8	1.53	<5	75	<5	1.57	3	11	128	1908	5.32	<10	0.92	806	17	<0.01	8	720	60	15	<20	74	0.02	<10	24	<10	<1	87
18	X09429	2.8	0.32	<5	50	<5	0.18	9	12	172	4324	5.73	<10	0.03	65	20	0.01	8	500	190	<5	<20	14	<0.01	<10	7	<10	<1	492
19	X09430	2.0	0.16	<5	50	<5	0.14	3	11	225	3934	5.07	<10	<0.01	72	11	0.01	8	<10	124	<5	<20	15	0.02	<10	3	<10	<1	58
20	X09431	<0.2	1.02	<5	270	15	0.73	<1	8	98	10	2.36	<10	0.52	561	2	0.14	5	950	24	<5	<20	113	0.12	<10	46	<10	7	40
21	X09432	2.5	0.31	<5	50	<5	0.19	3	12	157	4227	5.19	<10	0.03	67	14	0.01	7	570	84	<5	<20	15	<0.01	<10	6	<10	<1	93
22	X09433	2.7	0.22	15	45	<5	0.12	4	11	216	4879	4.49	<10	<0.01	44	12	0.01	10	200	114	10	<20	13	<0.01	<10	5	<10	<1	134
23	X09434	1.3	0.54	<5	50	<5	0.23	2	11	172	2621	4.58	<10	0.20	203	17	0.01	7	760	54	<5	<20	15	<0.01	<10	9	<10	<1	70
24	X09435	1.4	0.71	<5	50	<5	0.47	2	10	138	2479	4.37	<10	0.33	307	15	<0.01	6	820	72	<5	<20	18	0.01	<10	10	<10	<1	115
25	X09436	3.0	1.09	25	50	<5	1.06	3	23	58	2633	3.79	20	0.54	196	207	0.04	8	420	60	10	<20	48	0.03	<10	45	<10	5	255

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09437	1.7	0.53	<5	80	<5	0.39	7	14	154	2886	5.49	<10	0.19	290	18	0.01	7	740	88	<5	<20	24	0.01	<10	10	<10	<1	283
27	X09438	1.0	0.84	<5	60	<5	0.22	3	12	137	1743	5.23	<10	0.46	312	17	<0.01	7	890	50	<5	<20	18	0.02	<10	12	<10	1	136
28	X09439	2.8	0.56	<5	45	<5	0.23	2	10	183	3517	4.80	<10	0.20	164	18	0.01	8	790	98	<5	<20	8	<0.01	<10	9	<10	<1	88
29	X09440	1.8	1.10	<5	65	<5	0.26	2	9	103	2582	4.11	<10	0.58	361	20	<0.01	5	900	40	5	<20	12	<0.01	<10	13	<10	2	96
30	X09441	1.5	0.77	<5	60	<5	0.18	3	12	135	3115	4.78	<10	0.37	244	19	0.01	5	600	46	<5	<20	13	<0.01	<10	12	<10	<1	123
31	X09442	1.3	0.33	<5	45	<5	0.23	2	13	120	2673	5.05	<10	0.05	76	17	<0.01	5	850	40	<5	<20	14	<0.01	<10	6	<10	<1	47
32	X09443	1.5	0.26	<5	45	<5	0.26	4	13	126	2624	5.51	<10	<0.01	44	18	<0.01	6	980	46	<5	<20	11	<0.01	<10	5	<10	<1	117
33	X09444	1.2	0.40	<5	55	<5	0.24	4	13	120	1674	5.26	<10	0.09	134	23	<0.01	9	940	36	10	<20	11	<0.01	<10	8	<10	<1	86
34	X09445	1.4	0.31	<5	55	<5	0.20	2	13	161	3134	5.61	<10	<0.01	66	18	0.01	7	660	24	<5	<20	9	<0.01	<10	6	<10	<1	32
35	X09446	1.6	0.28	15	55	<5	0.18	1	10	231	3237	4.99	<10	<0.01	71	22	0.01	9	570	30	<5	<20	11	<0.01	<10	6	<10	<1	39
QC DATA:																													
Repeat:																													
1	X09412	1.4	0.82	20	55	<5	0.26	2	11	86	2196	4.58	<10	0.40	212	23	<0.01	5	1040	36	10	<20	13	0.01	<10	11	<10	2	108
10	X09421	2.2	0.24	<5	55	<5	0.20	3	16	164	3944	5.46	<10	<0.01	52	19	<0.01	7	570	36	<5	<20	15	<0.01	<10	6	<10	<1	54
19	X09430	2.0	0.14	<5	45	<5	0.14	2	10	212	3826	5.01	<10	<0.01	63	11	0.01	7	10	120	<5	<20	18	<0.01	<10	3	<10	<1	59
Resplit:																													
1	X09412	1.6	0.82	10	55	<5	0.22	3	12	93	2177	4.99	<10	0.37	198	24	<0.01	8	960	34	15	<20	8	0.01	<10	12	<10	2	93
Standard:																													
Pb114A		10.6	0.24	55	55	<5	1.82	39	3	5	2303	1.14	<10	0.09	1456	80	0.02	3	90	5500	15	<20	99	0.01	<10	7	<10	<1	6992

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5626
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5627

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

26-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07139
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09447	0.80	0.023
2	X09448	0.99	0.029
3	X09449	1.09	0.032
4	X09450	0.98	0.029
5	X09451	1.02	0.030
6	X09452	1.31	0.038
7	X09453	1.23	0.036
8	X09454	1.03	0.030
9	X09455	<0.03	<0.001
10	X09456	0.81	0.024
11	X09457	0.29	0.008
12	X09458	1.03	0.030
13	X09459	0.99	0.029
14	X09460	0.44	0.013
15	X09461	1.63	0.048
16	X09462	1.73	0.050
17	X09463	0.75	0.022
18	X09464	0.35	0.010
19	X09465	0.50	0.015
20	X09466	0.71	0.021
21	X09467	0.60	0.017
22	X09468	0.74	0.022
23	X09469	1.55	0.045
24	X09470	0.59	0.017
25	X09471	0.70	0.020
26	X09472	0.67	0.020
27	X09473	1.65	0.048
28	X09474	0.57	0.017
29	X09475	0.95	0.028

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5627 26-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X09476	0.71	0.021
31	X09477	0.42	0.012
32	X09478	0.41	0.012
33	X09479	0.51	0.015
34	X09480	0.38	0.011
35	X09481	0.56	0.016

QC DATA:

Repeat:

1	X09447	0.86	0.025
10	X09456	0.77	0.022
19	X09465	0.56	0.016

Resplits:

1	X09447	0.92	0.027

Standard:

OXK48		3.51	0.102

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

2-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5627

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07139
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09447	0.8	0.16	<5	35	<5	0.09	1	8	173	1978	3.11	<10	<0.01	58	10	0.01	4	250	26	<5	<20	7	<0.01	<10	7	<10	<1	72
2	X09448	1.2	0.18	<5	35	<5	0.13	2	8	181	2425	4.24	<10	<0.01	50	11	0.01	7	380	16	<5	<20	6	<0.01	<10	8	<10	<1	46
3	X09449	1.3	0.27	<5	40	<5	0.36	2	8	199	1904	4.81	<10	<0.01	59	14	0.01	7	1480	24	<5	<20	10	0.01	<10	9	<10	<1	61
4	X09450	1.3	0.18	<5	35	<5	0.15	1	9	245	2148	4.37	<10	<0.01	45	10	0.01	6	500	28	<5	<20	9	0.01	<10	6	<10	<1	28
5	X09451	1.1	0.25	<5	45	<5	0.19	2	8	213	2201	4.91	<10	<0.01	65	16	0.01	7	670	30	<5	<20	8	0.01	<10	7	<10	<1	54
6	X09452	1.5	0.28	10	40	<5	0.11	2	7	201	2627	4.06	<10	0.04	100	13	0.01	7	300	26	<5	<20	5	<0.01	<10	8	<10	<1	78
7	X09453	1.0	0.19	<5	40	<5	0.11	2	7	179	2555	4.33	<10	<0.01	50	14	0.01	6	280	28	<5	<20	12	<0.01	<10	6	<10	<1	43
8	X09454	1.1	0.23	5	40	<5	0.22	2	10	181	1698	4.67	<10	<0.01	47	12	0.01	11	840	18	5	<20	16	0.02	<10	6	<10	<1	19
9	X09455	<0.2	1.05	<5	265	15	0.60	<1	7	92	8	2.19	<10	0.60	531	3	0.14	8	900	16	5	<20	90	0.11	<10	47	<10	7	43
10	X09456	0.9	0.21	20	40	<5	0.15	<1	10	177	1563	4.35	<10	<0.01	49	8	0.01	2	520	28	<5	<20	4	0.01	<10	5	<10	<1	21
11	X09457	<0.2	3.14	30	85	20	0.32	2	34	52	41	6.75	<10	2.23	858	13	<0.01	7	1410	40	25	<20	10	0.03	<10	127	<10	4	174
12	X09458	2.4	0.24	50	45	<5	0.14	3	9	198	2497	5.72	<10	<0.01	39	12	0.01	8	440	28	10	<20	8	0.01	<10	7	<10	<1	41
13	X09459	1.6	0.51	<5	40	<5	0.19	2	16	151	2542	5.53	<10	0.17	191	12	0.01	9	630	24	10	<20	9	<0.01	<10	9	<10	<1	43
14	X09460	2.1	0.14	<5	40	<5	0.08	1	10	248	3261	3.59	<10	<0.01	79	13	0.01	8	130	12	<5	<20	5	<0.01	<10	8	<10	<1	28
15	X09461	2.2	0.17	15	45	<5	0.17	3	8	181	2536	4.41	<10	<0.01	51	8	0.01	6	600	14	<5	<20	11	0.01	<10	9	<10	<1	102
16	X09462	2.5	0.18	25	45	<5	0.12	2	9	197	3153	5.61	<10	<0.01	48	14	0.01	8	300	20	<5	<20	15	<0.01	<10	10	<10	<1	20
17	X09463	1.9	0.19	30	40	<5	0.22	2	8	196	2583	4.07	<10	<0.01	64	11	0.01	7	800	14	10	<20	16	<0.01	<10	9	<10	<1	20
18	X09464	1.8	0.14	25	40	<5	0.06	1	8	253	2821	3.24	<10	<0.01	52	15	0.01	7	90	32	<5	<20	14	<0.01	<10	7	<10	<1	18
19	X09465	1.9	0.16	5	80	<5	0.11	2	11	262	3357	5.00	<10	<0.01	63	10	0.01	9	240	20	<5	<20	29	<0.01	<10	9	<10	<1	30
20	X09466	2.1	0.23	<5	35	<5	0.09	2	8	229	2692	4.56	<10	0.02	79	12	0.01	7	170	16	<5	<20	8	<0.01	<10	9	<10	<1	29
21	X09467	2.3	0.20	<5	75	<5	0.11	5	10	183	2587	5.50	<10	<0.01	86	13	0.01	7	280	96	<5	<20	24	0.01	<10	10	<10	<1	231
22	X09468	2.0	0.24	20	50	<5	0.13	2	12	180	2288	5.75	<10	<0.01	77	17	0.01	5	420	20	<5	<20	11	0.01	<10	8	<10	<1	65
23	X09469	2.0	0.19	110	50	<5	0.13	3	10	212	2202	6.12	<10	<0.01	57	11	0.01	10	390	30	10	<20	14	0.01	<10	7	<10	<1	40
24	X09470	1.3	0.19	<5	45	<5	0.13	2	9	184	2172	4.76	<10	<0.01	81	15	0.01	7	390	24	<5	<20	14	<0.01	<10	8	<10	<1	10
25	X09471	1.3	0.37	<5	40	<5	0.10	1	9	227	2077	4.03	<10	0.12	243	32	0.01	6	210	10	<5	<20	8	0.01	<10	11	<10	<1	33

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09472	1.9	0.17	<5	40	<5	0.14	<1	11	199	3272	4.87	<10	<0.01	52	12	0.01	6	370	22	<5	<20	16	0.01	<10	7	<10	<1	14
27	X09473	<0.2	0.63	2185	90	15	0.73	17	28	24	64	4.85	20	1.91	737	5	0.16	102	1170	16	10	<20	58	0.08	<10	22	<10	10	56
28	X09474	1.4	0.12	<5	35	<5	0.04	<1	7	208	2963	2.91	<10	<0.01	67	7	0.01	4	<10	16	<5	<20	17	<0.01	<10	5	<10	<1	14
29	X09475	1.6	0.21	<5	45	<5	0.13	3	9	172	2372	5.41	<10	<0.01	77	14	0.01	10	390	24	10	<20	19	<0.01	<10	8	<10	<1	29
30	X09476	1.8	0.20	<5	35	<5	0.08	1	7	195	2280	4.43	<10	<0.01	64	9	0.01	7	160	12	<5	<20	9	<0.01	<10	8	<10	<1	12
31	X09477	1.4	0.20	<5	40	<5	0.12	2	8	201	2070	4.63	<10	<0.01	53	17	0.01	7	330	16	<5	<20	10	<0.01	<10	8	<10	<1	23
32	X09478	1.6	0.17	<5	40	<5	0.09	2	8	207	2856	4.28	<10	<0.01	84	13	0.01	7	140	20	<5	<20	7	<0.01	<10	7	<10	<1	17
33	X09479	1.8	0.15	20	90	<5	0.06	2	6	224	1877	3.75	<10	<0.01	77	9	<0.01	7	110	16	<5	<20	42	<0.01	<10	6	<10	<1	30
34	X09480	3.2	0.14	105	60	<5	0.05	4	6	209	1577	3.08	<10	<0.01	33	16	<0.01	6	80	90	20	<20	66	<0.01	<10	4	<10	<1	276
35	X09481	2.5	0.19	20	40	<5	0.05	3	9	206	2257	4.77	<10	<0.01	55	19	0.01	8	<10	28	10	<20	12	<0.01	<10	6	<10	<1	78
QC DATA:																													
Repeat:																													
1	X09447	0.9	0.16	<5	40	<5	0.09	1	8	176	2022	3.13	<10	0.01	55	11	0.01	5	240	26	<5	<20	8	<0.01	<10	7	<10	<1	73
10	X09456	0.8	0.19	20	45	<5	0.15	2	10	175	1605	4.43	<10	<0.01	50	15	0.01	8	520	28	<5	<20	8	<0.01	<10	6	<10	<1	20
19	X09465	1.8	0.14	10	80	<5	0.11	2	10	249	3298	4.92	<10	<0.01	62	10	0.01	11	230	18	5	<20	28	<0.01	<10	8	<10	<1	30
Resplit:																													
1	X09447	1.1	0.17	<5	35	<5	0.09	2	8	175	1977	3.30	<10	0.02	63	11	0.01	8	250	32	<5	<20	12	<0.01	<10	7	<10	<1	78
Standard:																													
PB113A		11.6	0.26	45	65	<5	1.72	37	2	5	2250	1.02	<10	0.11	1477	65	0.02	3	90	5518	25	<20	89	<0.01	<10	8	<10	<1	6990

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/1744S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5628

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

26-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07140
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09482	1.05	0.031
2	X09483	0.34	0.010
3	X09484	0.38	0.011
4	X09485	0.53	0.015
5	X09486	0.46	0.013
6	X09487	0.67	0.020
7	X09488	0.76	0.022
8	X09489	0.77	0.022
9	X09490	0.96	0.028
10	X09491	0.73	0.021
11	X09492	<0.03	<0.001
12	X09493	0.36	0.010
13	X09494	0.72	0.021
14	X09495	0.45	0.013
15	X09496	0.55	0.016
16	X09497	1.10	0.032
17	X09498	0.54	0.016
18	X09499	0.27	0.008
19	X09500	0.32	0.009
20	X09501	0.20	0.006
21	X09502	0.47	0.014
22	X09503	0.34	0.010
23	X09504	0.74	0.022
24	X09505	0.52	0.015
25	X09506	0.86	0.025
26	X09507	0.64	0.019
27	X09508	1.03	0.030
28	X09509	0.61	0.018
29	X09510	0.71	0.021

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5628 26-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X09511	0.91	0.027
31	X09512	0.99	0.029
32	X09513	0.70	0.020
33	X09514	0.47	0.014
34	X09515	0.60	0.017
35	X09516	0.55	0.016

QC DATA:

Repeat:

1	X09482	0.99	0.029
9	X09490	1.00	0.029
10	X09491	0.75	0.022
19	X09500	0.29	0.008

Resplits:

1	X09482	0.95	0.028

Standard:

OXK48		3.57	0.104

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

2-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5628

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07140
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09482	1.6	0.19	15	55	<5	0.05	2	13	179	2366	6.07	<10	<0.01	70	13	0.01	9	<10	26	<5	<20	27	0.01	<10	7	<10	<1	31
2	X09483	1.3	0.19	<5	35	<5	0.06	2	10	206	2084	4.02	<10	<0.01	56	23	0.01	8	60	36	<5	<20	12	<0.01	<10	6	<10	<1	117
3	X09484	1.1	0.19	<5	40	<5	0.09	2	7	200	1714	3.43	<10	<0.01	39	29	0.01	8	270	24	<5	<20	5	<0.01	<10	5	<10	<1	40
4	X09485	0.9	0.24	<5	45	<5	0.21	2	7	204	1540	3.82	<10	<0.01	47	41	0.01	9	770	24	<5	<20	8	<0.01	<10	7	<10	<1	30
5	X09486	0.9	0.19	<5	50	<5	0.15	2	10	196	1962	4.15	<10	<0.01	40	41	0.01	8	500	14	<5	<20	7	<0.01	<10	5	<10	<1	23
6	X09487	0.9	0.24	<5	50	<5	0.19	2	8	199	1807	4.44	<10	<0.01	42	36	0.01	7	670	38	<5	<20	11	0.01	<10	7	<10	<1	59
7	X09488	2.7	0.21	85	40	<5	0.10	8	8	264	1849	4.12	<10	<0.01	42	23	0.01	8	280	174	60	<20	21	<0.01	<10	6	<10	<1	512
8	X09489	1.8	0.24	10	40	<5	0.34	2	11	188	1831	4.44	<10	<0.01	42	26	0.01	7	1320	48	15	<20	13	<0.01	<10	6	<10	<1	47
9	X09490	1.1	0.23	<5	35	<5	0.22	3	9	189	1687	3.55	<10	<0.01	51	33	0.01	5	810	146	<5	<20	16	0.01	<10	6	<10	<1	167
10	X09491	1.3	0.26	<5	45	<5	0.24	2	9	184	2013	4.31	<10	<0.01	45	144	0.01	6	880	46	<5	<20	9	0.02	<10	6	<10	<1	72
11	X09492	<0.2	1.11	10	260	20	0.62	<1	7	106	9	2.12	<10	0.62	522	5	0.14	7	840	16	10	<20	108	0.11	<10	47	<10	8	40
12	X09493	1.3	0.19	20	35	<5	0.22	2	9	195	1488	2.96	<10	<0.01	34	36	0.01	6	860	32	<5	<20	15	<0.01	<10	6	<10	1	64
13	X09494	1.3	0.20	10	35	<5	0.22	3	6	196	1777	3.82	<10	<0.01	37	17	0.01	8	810	54	<5	<20	16	<0.01	<10	6	<10	<1	122
14	X09495	1.2	0.20	<5	40	<5	0.20	2	8	208	1448	3.75	<10	<0.01	30	33	0.01	7	790	30	<5	<20	18	<0.01	<10	6	<10	<1	44
15	X09496	1.3	0.19	<5	35	<5	0.08	2	7	209	2001	3.53	<10	<0.01	39	35	0.01	8	200	22	<5	<20	10	<0.01	<10	6	<10	<1	36
16	X09497	1.4	0.19	<5	45	<5	0.11	1	10	187	2079	4.57	<10	<0.01	31	39	0.01	8	300	16	<5	<20	10	<0.01	<10	5	<10	<1	7
17	X09498	1.2	0.22	<5	40	<5	0.12	1	9	218	1510	3.80	<10	<0.01	46	18	0.01	7	410	24	<5	<20	13	<0.01	<10	6	<10	<1	25
18	X09499	1.3	0.16	10	40	<5	0.10	1	8	198	1511	3.20	<10	<0.01	30	18	0.01	6	300	16	<5	<20	9	<0.01	<10	5	<10	<1	29
19	X09500	1.1	0.20	5	40	<5	0.10	2	9	225	1498	3.61	<10	<0.01	37	16	0.01	8	300	18	<5	<20	11	<0.01	<10	6	<10	<1	30
20	X09501	2.0	0.18	55	35	<5	0.13	4	9	207	837	3.23	<10	<0.01	28	27	0.01	7	510	18	30	<20	15	<0.01	<10	4	<10	<1	156
21	X09502	4.4	0.20	15	40	<5	0.15	2	8	183	1873	3.71	<10	<0.01	31	26	0.01	6	500	42	20	<20	24	<0.01	<10	6	<10	<1	35
22	X09503	1.7	0.16	20	55	<5	0.13	1	8	193	1557	3.19	<10	<0.01	33	39	0.01	7	450	28	10	<20	51	<0.01	<10	6	<10	<1	17
23	X09504	2.4	0.21	30	35	<5	0.13	2	6	184	2323	3.64	<10	<0.01	36	52	0.01	6	380	24	10	<20	23	<0.01	<10	6	<10	<1	32
24	X09505	7.2	0.19	145	35	<5	0.15	5	8	215	1590	3.61	<10	<0.01	74	39	0.01	7	490	84	80	<20	57	<0.01	<10	6	<10	<1	155
25	X09506	2.3	0.22	25	45	<5	0.22	3	9	153	1858	5.45	<10	<0.01	36	44	0.01	7	780	78	10	<20	26	0.01	<10	6	<10	<1	91

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09507	1.6	0.20	<5	35	<5	0.13	2	8	210	1647	4.05	<10	<0.01	42	34	0.01	8	420	40	<5	<20	12	<0.01	<10	6	<10	<1	41
27	X09508	2.2	0.21	<5	40	<5	0.14	7	11	158	1769	5.32	<10	<0.01	34	88	0.01	7	460	154	<5	<20	17	0.01	<10	6	<10	<1	345
28	X09509	1.3	0.22	<5	35	<5	0.12	1	11	199	1356	4.52	<10	<0.01	61	45	0.01	6	370	28	<5	<20	20	0.01	<10	6	<10	<1	37
29	X09510	1.0	0.22	<5	35	<5	0.11	2	10	173	1383	4.42	<10	<0.01	41	34	0.01	4	330	26	<5	<20	12	0.02	<10	6	<10	<1	50
30	X09511	0.2	0.88	1430	95	5	0.90	11	30	23	60	4.71	20	2.23	650	6	0.23	111	1170	14	25	<20	58	0.10	<10	26	<10	12	54
31	X09512	0.8	0.23	<5	35	<5	0.11	2	11	202	1100	4.39	<10	<0.01	44	63	0.01	7	350	32	<5	<20	9	0.01	<10	7	<10	<1	21
32	X09513	1.9	0.29	<5	40	<5	0.08	1	10	214	2098	3.89	<10	0.06	87	54	0.01	7	190	18	<5	<20	12	<0.01	<10	8	<10	<1	16
33	X09514	1.0	0.20	<5	35	<5	0.11	1	11	199	1498	4.25	<10	<0.01	36	55	0.01	6	340	24	<5	<20	12	0.01	<10	6	<10	<1	22
34	X09515	1.4	0.22	<5	45	<5	0.16	3	11	175	1221	5.12	<10	<0.01	33	45	0.01	8	570	56	<5	<20	16	0.01	<10	5	<10	<1	78
35	X09516	1.0	0.47	<5	45	<5	0.15	2	9	181	1130	4.63	<10	0.21	180	41	0.01	5	540	102	<5	<20	11	0.02	<10	8	<10	<1	69
QC DATA:																													
Repeat:																													
1	X09482	2.0	0.19	10	55	<5	0.05	2	12	179	2440	5.91	<10	<0.01	68	11	0.01	8	<10	24	<5	<20	25	0.01	<10	7	<10	<1	31
10	X09491	1.4	0.25	<5	40	<5	0.24	2	9	181	1995	4.23	<10	<0.01	44	140	0.01	6	870	44	<5	<20	10	<0.01	<10	7	<10	<1	70
19	X09500	1.3	0.20	<5	40	<5	0.10	2	9	228	1543	3.68	<10	<0.01	37	16	0.01	8	310	18	<5	<20	10	<0.01	<10	6	<10	<1	31
Resplit:																													
1	X09482	1.8	0.19	10	50	<5	0.04	3	11	175	2410	5.98	<10	<0.01	70	12	0.01	11	<10	22	<5	<20	31	0.01	<10	6	<10	<1	29
Standard:																													
PB113A		11.5	0.28	45	65	<5	1.63	39	2	5	2227	1.03	<10	0.11	1596	78	0.02	3	<10	5452	25	<20	86	<0.01	<10	8	<10	<1	6937

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/1744S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5629

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

8-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07141
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35908	0.72	0.021
2	G35909	0.58	0.017
3	G35910	0.64	0.019
4	G35911	0.55	0.016
5	G35912	0.56	0.016
6	G35913	0.60	0.017
7	G35914	0.43	0.013
8	G35915	0.54	0.016
9	G35916	0.40	0.012
10	G35917	0.50	0.015
11	G35918	0.72	0.021
12	G35919	0.63	0.018
13	G35920	0.51	0.015
14	G35921	0.65	0.019
15	G35922	1.01	0.029
16	G35923	0.54	0.016
17	G35924	0.70	0.020
18	G35925	<0.03	<0.001
19	G35926	1.03	0.030
20	G35927	0.88	0.026
21	G35928	0.93	0.027
22	G35929	0.69	0.020
23	G35930	0.44	0.013
24	G35931	0.73	0.021
25	G35932	0.99	0.029
26	G35933	0.63	0.018
27	G35934	0.96	0.028
28	G35935	0.89	0.026
29	G35936	0.28	0.008

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5629 8-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	G35937	0.44	0.013
31	G35938	0.73	0.021
32	G35939	0.71	0.021
33	G35940	0.88	0.026
34	G35941	0.97	0.028
35	G35942	0.92	0.027

QC DATA:

Repeat:

1	G35908	0.65	0.019
10	G35917	0.55	0.016
19	G35926	1.00	0.029

Resplits:

1	G35908	0.62	0.018

Standard:

OXI54		1.87	0.055

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

2-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5629

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1


No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07141
Submitted by: Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35908	1.3	1.22	<5	35	<5	4.54	2	18	75	1062	4.70	<10	1.13	805	94	0.02	5	1220	46	5	<20	461	0.02	<10	35	<10	2	90
2	G35909	1.0	1.62	<5	30	<5	3.96	2	19	64	897	4.97	<10	1.42	790	155	0.02	6	1210	36	10	<20	379	0.02	<10	43	<10	<1	83
3	G35910	1.0	1.18	10	35	<5	4.29	2	18	58	1090	4.69	<10	1.04	591	264	0.02	5	1270	44	<5	<20	413	0.02	<10	36	<10	1	74
4	G35911	0.7	1.74	<5	30	<5	5.01	2	17	57	844	4.23	<10	1.61	1002	81	0.02	5	1290	32	10	<20	436	0.02	<10	45	<10	2	113
5	G35912	1.0	1.66	<5	30	<5	4.46	2	19	57	875	4.73	<10	1.43	1001	97	0.02	5	1580	32	5	<20	422	0.02	<10	55	<10	2	123
6	G35913	1.0	1.36	5	30	<5	4.80	2	17	98	635	4.51	<10	1.08	1083	119	0.02	8	1710	50	10	<20	497	0.02	<10	59	<10	3	141
7	G35914	0.9	1.39	<5	30	<5	5.29	2	15	62	717	4.42	<10	1.04	957	58	0.02	6	1690	46	<5	<20	568	0.02	<10	65	<10	3	131
8	G35915	1.0	1.84	10	45	<5	6.18	2	17	67	817	4.65	<10	1.66	1557	50	0.03	5	1590	44	10	<20	525	0.03	<10	82	<10	3	158
9	G35916	1.4	1.38	15	30	<5	5.59	2	17	71	921	4.41	<10	1.19	1422	77	0.01	5	1360	56	5	<20	476	0.03	<10	38	<10	2	126
10	G35917	1.8	1.11	10	30	<5	4.58	4	22	82	1455	5.31	<10	1.04	762	111	0.02	8	1280	88	20	<20	492	0.02	<10	37	<10	<1	140
11	G35918	1.2	1.86	<5	40	<5	6.34	2	19	67	1126	4.78	<10	1.56	1382	82	0.02	5	1450	102	10	<20	574	0.03	<10	53	<10	3	155
12	G35919	1.0	2.11	<5	35	<5	5.41	7	16	87	866	5.48	<10	1.71	1020	104	0.01	7	1520	50	10	<20	566	0.02	<10	59	<10	<1	268
13	G35920	0.7	1.64	<5	25	<5	4.73	2	19	71	686	5.10	<10	1.38	765	101	0.01	7	1680	46	10	<20	465	0.02	<10	51	<10	<1	149
14	G35921	1.3	1.31	<5	35	<5	2.88	13	15	90	1189	4.19	<10	1.16	584	101	0.01	7	1350	48	10	<20	270	0.02	<10	36	<10	1	267
15	G35922	2.0	0.87	<5	40	<5	2.24	2	14	93	1565	4.43	<10	0.76	569	82	0.01	7	830	58	<5	<20	184	0.01	<10	19	<10	<1	151
16	G35923	1.6	0.87	<5	25	<5	3.24	7	10	87	1264	3.73	<10	0.98	1048	69	0.01	6	910	84	10	<20	263	0.02	<10	25	<10	<1	259
17	G35924	1.3	1.19	<5	35	<5	1.72	4	10	92	1347	3.41	<10	1.09	508	78	0.02	8	1070	62	10	<20	189	0.03	<10	34	<10	2	218
18	G35925	<0.2	1.04	<5	260	15	0.60	<1	7	106	7	2.20	<10	0.60	535	<1	0.12	5	900	16	<5	<20	96	0.11	<10	46	<10	6	42
19	G35926	2.1	1.13	5	35	<5	1.91	15	13	118	1646	4.07	<10	1.19	832	87	0.01	8	1070	270	<5	<20	169	0.02	<10	29	<10	2	515
20	G35927	1.9	1.87	<5	45	<5	1.15	1	16	84	1652	4.65	<10	2.00	976	76	0.01	8	1170	68	10	<20	58	0.02	<10	50	<10	2	99
21	G35928	1.5	2.09	<5	55	<5	0.97	2	19	109	1643	4.94	<10	1.76	596	111	0.03	11	1110	44	15	<20	43	0.02	<10	65	<10	2	86
22	G35929	1.2	1.84	<5	50	<5	1.14	2	15	70	1370	4.22	<10	1.75	878	70	0.03	9	1140	36	20	<20	52	0.01	<10	56	<10	2	78
23	G35930	1.3	1.43	<5	40	<5	1.38	2	14	91	1627	4.13	<10	1.64	1081	68	0.02	8	1050	46	15	<20	48	0.02	<10	43	<10	2	102
24	G35931	1.5	1.23	<5	40	<5	1.76	2	15	86	1645	4.16	<10	1.54	1087	92	0.01	9	950	84	15	<20	78	0.03	<10	29	<10	2	163
25	G35932	3.9	1.09	45	85	<5	0.73	3	17	58	3287	3.91	20	0.50	268	270	0.04	13	390	140	25	<20	33	0.03	<10	43	<10	6	153

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35933	1.3	1.59	10	55	<5	1.79	2	15	78	1104	4.73	<10	1.74	1094	75	0.01	7	1310	40	10	<20	46	0.02	<10	38	<10	3	111
27	G35934	1.5	1.49	10	45	<5	1.57	1	14	76	1671	4.24	<10	1.74	1048	70	0.01	7	1210	32	15	<20	29	0.02	<10	37	<10	2	110
28	G35935	1.8	1.01	<5	45	<5	0.71	2	18	77	2658	4.68	<10	0.97	411	42	0.01	8	1150	36	10	<20	17	<0.01	<10	26	<10	<1	116
29	G35936	1.6	0.60	5	40	<5	0.82	2	13	84	1673	3.95	<10	0.63	460	76	0.01	6	1180	74	5	<20	24	0.01	<10	14	<10	1	109
30	G35937	1.9	1.19	<5	45	<5	1.27	2	12	71	2223	4.91	<10	1.29	814	63	0.01	6	1400	50	<5	<20	35	0.01	<10	29	<10	1	93
31	G35938	1.1	1.52	<5	50	<5	1.84	2	13	79	1235	4.34	<10	1.84	1105	126	0.01	7	1350	38	10	<20	42	0.02	<10	44	<10	2	83
32	G35939	1.0	1.91	<5	50	<5	2.21	2	14	96	1079	4.70	<10	2.33	1180	113	0.01	8	1460	40	15	<20	60	0.02	<10	56	<10	3	89
33	G35940	2.1	1.19	<5	50	<5	1.66	3	13	124	2032	4.22	<10	1.42	1194	68	0.01	10	1020	44	20	<20	41	0.01	<10	31	<10	2	80
34	G35941	1.9	1.42	<5	55	<5	1.62	1	12	100	1622	3.97	<10	1.56	1476	38	0.01	5	990	62	10	<20	35	0.02	<10	23	<10	3	134
35	G35942	1.6	1.37	10	65	<5	1.43	1	10	83	1312	3.73	<10	1.42	1060	67	0.01	4	1110	34	10	<20	31	0.02	<10	20	<10	3	98
QC DATA:																													
Repeat:																													
1	G35908	1.2	1.23	<5	35	<5	4.48	2	18	77	1025	4.68	<10	1.12	798	101	0.02	5	1220	46	<5	<20	453	0.02	<10	35	<10	1	92
10	G35917	1.9	1.11	15	30	<5	4.42	3	22	85	1417	5.36	<10	1.01	760	108	0.02	8	1320	100	15	<20	467	0.02	<10	37	<10	1	150
19	G35926	2.3	1.18	<5	40	<5	1.94	16	13	125	1662	4.16	<10	1.21	849	100	0.01	8	1110	282	5	<20	178	0.02	<10	30	<10	2	532
Resplit:																													
1	G35908	1.3	1.24	<5	35	<5	4.76	3	17	76	1065	4.81	<10	1.09	802	98	0.02	10	1220	54	5	<20	461	0.02	<10	38	<10	2	102
Standard:																													
PB113A		10.9	0.27	55	60	<5	1.72	39	3	6	2303	1.09	<10	0.11	1439	74	0.02	4	70	5544	30	<20	90	<0.01	<10	8	<10	<1	6963

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish



ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
di/1744S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5631

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

8-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07142
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35943	1.14	0.033
2	G35944	0.66	0.019
3	G35945	0.49	0.014
4	G35946	0.59	0.017
5	G35947	0.78	0.023
6	G35948	0.79	0.023
7	G35949	0.43	0.013
8	G35950	0.74	0.022
9	G35951	0.29	0.008
10	G35952	0.25	0.007
11	G35953	0.60	0.017
12	G35954	0.13	0.004
13	G35955	0.30	0.009
14	G35956	0.33	0.010
15	G35957	0.13	0.004
16	G35958	0.19	0.006
17	G35959	0.36	0.010
18	G35960	0.18	0.005
19	G35961	0.27	0.008
20	G35962	1.73	0.050
21	G35963	0.46	0.013
22	G35964	0.67	0.020
23	G35965	0.17	0.005
24	G35966	0.08	0.002
25	G35967	0.07	0.002
26	G35968	0.38	0.011
27	G35969	0.37	0.011
28	G35970	0.57	0.017
29	G35971	<0.03	<0.001

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5631 8-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	G35972	0.36	0.010
31	G35973	0.66	0.019
32	G35974	0.48	0.014
33	G35975	0.13	0.004
34	G35976	0.34	0.010
35	G35977	0.89	0.026

QC DATA:

Repeat:

1	G35943	1.19	0.035
10	G35952	0.25	0.007
19	G35961	0.25	0.007

Resplits:

1	G35943	1.07	0.031

Standard:

OXI54		1.87	0.055

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

2-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5631

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07142
Submitted by: Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35943	1.1	1.85	10	60	<5	1.07	1	14	92	1316	4.35	<10	1.88	1098	56	0.03	5	1080	48	15	<20	22	0.02	<10	35	<10	2	98
2	G35944	1.2	1.34	<5	50	<5	1.54	2	14	79	1018	5.05	<10	1.54	1648	26	0.03	6	1140	86	5	<20	34	0.03	<10	28	<10	3	80
3	G35945	0.8	1.75	<5	60	<5	0.90	2	10	91	789	3.89	<10	1.80	1106	51	0.04	4	1150	40	10	<20	15	0.02	<10	38	<10	3	106
4	G35946	1.1	1.57	10	55	<5	1.56	1	12	75	937	3.67	<10	1.88	1173	46	0.02	5	1100	42	15	<20	28	0.02	<10	29	<10	3	75
5	G35947	1.2	1.57	<5	60	<5	1.48	1	10	74	1245	3.68	<10	1.86	1104	54	0.02	4	1060	46	10	<20	29	0.02	<10	29	<10	3	80
6	G35948	0.7	1.66	5	70	<5	1.48	1	9	61	706	3.78	<10	1.92	1201	33	0.02	5	1210	36	20	<20	33	0.02	<10	33	<10	5	95
7	G35949	1.9	0.42	<5	45	<5	1.20	4	15	114	1855	5.24	<10	0.47	601	45	0.01	6	660	74	<5	<20	26	0.01	<10	7	<10	<1	97
8	G35950	2.0	0.58	<5	45	<5	0.72	6	13	118	1611	5.00	<10	0.44	397	54	0.02	9	930	90	15	<20	17	<0.01	<10	10	<10	<1	184
9	G35951	2.4	0.49	<5	40	<5	1.01	2	11	143	464	4.41	<10	0.48	653	46	0.02	6	660	38	<5	<20	27	0.02	<10	7	<10	<1	41
10	G35952	13.7	0.24	15	45	10	0.12	1	8	116	105	4.12	<10	<0.01	22	42	0.02	4	480	28	5	<20	9	0.01	<10	4	<10	<1	14
11	G35953	6.8	0.31	50	45	15	0.29	5	11	104	301	4.78	<10	<0.01	27	49	0.02	7	1280	66	50	<20	12	0.01	<10	4	<10	<1	278
12	G35954	0.7	0.28	<5	45	5	0.24	<1	5	122	150	2.70	<10	0.01	37	32	0.02	4	1040	32	<5	<20	9	0.02	<10	4	<10	<1	17
13	G35955	3.1	1.21	40	60	<5	1.00	3	22	60	2670	3.61	20	0.64	196	211	0.04	10	450	72	15	<20	60	0.04	<10	48	<10	8	275
14	G35956	1.6	0.36	<5	45	<5	0.30	2	9	97	1023	4.16	<10	0.09	57	28	0.02	5	1120	42	<5	<20	13	<0.01	<10	7	<10	2	84
15	G35957	1.2	0.33	<5	50	<5	0.32	2	10	107	1412	3.62	<10	0.08	70	37	0.02	6	1130	54	<5	<20	13	<0.01	<10	5	<10	2	103
16	G35958	1.0	0.43	<5	50	<5	0.52	1	11	109	1031	4.05	<10	0.25	250	28	0.02	5	1070	22	<5	<20	16	0.01	<10	6	<10	2	30
17	G35959	3.0	0.31	<5	50	<5	0.47	2	11	117	1206	5.13	<10	0.14	189	42	0.02	7	950	40	<5	<20	15	0.01	<10	4	<10	<1	29
18	G35960	1.6	0.50	<5	45	<5	0.95	2	13	98	1500	4.42	<10	0.48	555	44	0.02	6	1030	128	10	<20	29	0.01	<10	7	<10	2	40
19	G35961	1.3	0.61	<5	45	<5	1.11	5	13	84	1273	4.39	<10	0.63	611	46	0.02	5	1060	92	5	<20	34	0.02	<10	9	<10	2	273
20	G35962	6.5	0.42	<5	45	<5	0.55	10	15	97	2278	5.63	<10	0.20	199	22	0.02	8	990	96	<5	<20	22	0.01	<10	7	<10	<1	539
21	G35963	1.8	0.56	<5	55	<5	1.29	12	12	121	1125	4.60	<10	0.70	764	31	0.02	8	1020	90	<5	<20	37	0.02	<10	8	<10	2	556
22	G35964	2.5	0.58	<5	45	<5	0.70	6	11	154	1458	3.91	<10	0.45	432	34	0.02	5	880	48	5	<20	23	0.01	<10	8	<10	1	324
23	G35965	1.5	0.43	<5	45	<5	0.41	4	17	113	793	5.35	<10	0.30	243	35	0.02	6	870	92	<5	<20	14	0.02	<10	6	<10	<1	193
24	G35966	1.8	0.37	<5	45	<5	0.31	7	13	119	1388	4.69	<10	0.09	86	25	0.02	6	1080	84	<5	<20	16	0.01	<10	5	<10	<1	402
25	G35967	1.0	0.40	<5	45	<5	0.29	2	13	99	986	4.08	<10	0.14	82	29	0.02	6	1060	34	<5	<20	12	<0.01	<10	5	<10	2	33

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	G35968	1.1	0.42	<5	50	<5	0.27	3	10	106	1004	4.28	<10	0.11	56	59	0.03	6	1040	28	<5	<20	18	0.01	<10	6	<10	1	89
27	G35969	1.0	0.40	15	50	<5	0.39	2	12	111	1134	4.05	<10	0.19	299	48	0.02	5	1030	42	15	<20	19	0.01	<10	7	<10	2	67
28	G35970	1.7	0.57	20	45	<5	0.46	2	12	127	1427	4.25	<10	0.38	437	33	0.02	8	1050	38	15	<20	21	0.03	<10	8	<10	2	71
29	G35971	<0.2	1.06	5	275	30	0.63	1	7	94	8	2.24	<10	0.63	557	6	0.12	8	950	20	15	<20	96	0.10	<10	49	<10	7	44
30	G35972	1.5	0.44	<5	45	<5	0.27	2	12	130	1605	4.39	<10	0.20	90	34	0.02	7	900	36	<5	<20	13	<0.01	<10	7	<10	<1	32
31	G35973	1.1	0.50	<5	40	<5	0.36	2	11	124	1495	4.44	<10	0.22	215	23	0.02	6	1050	34	<5	<20	17	0.01	<10	9	<10	2	63
32	G35974	0.8	0.60	<5	45	<5	0.61	2	12	93	920	4.39	<10	0.43	365	26	0.02	6	950	22	<5	<20	24	0.01	<10	9	<10	1	68
33	G35975	0.6	0.47	<5	45	<5	0.38	4	10	95	1185	3.88	<10	0.20	126	25	0.02	6	1070	36	<5	<20	16	<0.01	<10	7	<10	2	179
34	G35976	0.9	0.55	<5	40	<5	0.91	1	13	102	1528	4.67	<10	0.36	508	23	0.02	6	1010	32	<5	<20	34	0.02	<10	8	<10	2	35
35	G35977	1.6	0.62	<5	50	<5	1.35	1	13	84	1235	4.90	<10	0.70	1055	21	0.02	5	1060	20	<5	<20	42	0.02	<10	9	<10	2	50
QC DATA:																													
Repeat:																													
1	G35943	1.2	1.84	10	65	<5	1.07	1	14	92	1311	4.31	<10	1.87	1088	55	0.03	5	1090	48	15	<20	22	0.02	<10	34	<10	3	96
10	G35952	13.8	0.23	15	45	10	0.12	2	8	116	108	4.12	<10	<0.01	20	43	0.02	7	490	28	5	<20	9	0.01	<10	4	<10	<1	14
19	G35961	1.4	0.60	5	50	<5	1.12	5	13	83	1316	4.43	<10	0.63	620	46	0.02	5	1070	94	10	<20	33	0.02	<10	9	<10	2	279
Resplit:																													
1	G35943	1.2	1.79	<5	60	5	1.16	3	14	87	1374	4.40	<10	1.88	1118	56	0.03	8	1020	54	20	<20	25	0.02	<10	33	<10	3	93
Standard:																													
Pb113A		10.7	0.28	55	65	<5	1.70	41	2	6	2318	1.09	<10	0.12	1444	72	0.02	3	70	5438	30	<20	86	<0.01	<10	8	<10	<1	7110

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/1744S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5632

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

7-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07143
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G35978	0.18	0.005
2	G35979	0.17	0.005
3	G35980	0.44	0.013
4	G35981	0.21	0.006
5	G35982	0.26	0.008
6	G35983	0.41	0.012
7	G35984	0.36	0.010
8	G35985	1.34	0.039
9	G35986	0.87	0.025
10	G35987	0.53	0.015
11	G35988	0.27	0.008
12	G35989	<0.03	<0.001
13	G35990	0.47	0.014
14	G35991	0.56	0.016
15	G35992	0.28	0.008
16	G35993	1.18	0.034
17	G35994	0.34	0.010
18	G35995	0.51	0.015
19	G35996	0.14	0.004
20	G35997	1.82	0.053
21	G35998	0.10	0.003
22	G35999	0.27	0.008
23	G36000	0.13	0.004
24	X05001	0.14	0.004
25	X05002	0.10	0.003

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AK7-5632 7-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X05003	0.08	0.002
27	X05004	0.09	0.003
28	X05005	0.10	0.003
29	X05006	0.03	0.001
30	X05007	0.12	0.003
31	X05008	0.12	0.003
32	X05009	0.09	0.003
33	X05010	0.11	0.003
34	X05011	0.14	0.004
35	X05012	0.16	0.005
QC DATA:			
Repeat:			
1	G35978	0.18	0.005
8	G35985	1.47	0.043
9	G35986	0.92	0.027
10	G35987	0.52	0.015
16	G35993	1.15	0.034
19	G35996	0.12	0.003
Resplits:			
1	G35978	0.23	0.007
Standard:			
OXi54		1.85	0.054

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
XLS/07

14-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5632

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07143
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G35978	1.8	0.54	<5	45	<5	0.40	2	10	96	1177	3.36	<10	0.27	181	35	0.02	4	1040	18	<5	<20	20	<0.01	<10	8	<10	<1	45
2	G35979	3.4	0.43	<5	45	<5	0.59	2	10	123	1676	3.73	<10	0.32	438	25	0.02	5	830	24	<5	<20	27	0.01	<10	8	<10	<1	52
3	G35980	1.4	0.43	<5	45	<5	0.63	2	10	99	1188	3.71	<10	0.32	349	17	0.02	5	950	40	<5	<20	23	0.01	<10	6	<10	1	53
4	G35981	2.5	0.44	<5	45	<5	0.77	1	11	127	1606	4.18	<10	0.33	425	20	0.02	6	930	30	<5	<20	29	0.02	<10	7	<10	1	35
5	G35982	4.8	0.30	<5	45	<5	0.52	2	9	123	1489	3.29	<10	0.16	228	21	0.02	5	730	30	<5	<20	23	<0.01	<10	5	<10	<1	35
6	G35983	16.7	0.39	20	45	<5	1.07	2	9	117	1992	3.27	<10	0.54	696	14	0.01	5	790	70	35	<20	40	0.02	<10	6	<10	2	85
7	G35984	7.0	0.52	<5	50	<5	0.69	2	15	129	2404	4.29	<10	0.37	391	13	0.02	6	820	18	<5	<20	24	0.01	<10	8	<10	1	40
8	G35985	4.5	1.03	<5	55	<5	1.31	2	15	81	3322	4.28	<10	0.87	637	18	0.01	4	900	20	5	<20	47	0.01	<10	13	<10	2	56
9	G35986	3.5	0.86	<5	40	<5	1.69	2	10	111	2090	3.63	<10	0.99	921	19	0.01	4	860	34	10	<20	50	0.02	<10	11	<10	2	60
10	G35987	1.6	0.78	<5	55	<5	1.69	2	9	92	1792	3.17	<10	1.00	894	25	0.01	4	840	26	<5	<20	49	0.02	<10	11	<10	2	64
11	G35988	1.3	0.58	<5	50	<5	1.28	2	9	107	1126	2.92	<10	0.64	590	18	0.01	7	1080	34	15	<20	35	0.01	<10	8	<10	3	42
12	G35989	<0.2	1.05	5	255	25	0.59	<1	7	100	6	2.17	<10	0.64	540	4	0.10	7	930	18	5	<20	84	0.13	<10	48	<10	5	39
13	G35990	3.4	0.53	<5	50	<5	1.38	2	10	120	3398	3.65	<10	0.69	659	13	0.02	5	580	34	10	<20	44	0.01	<10	9	<10	1	67
14	G35991	1.9	0.61	<5	35	<5	1.89	2	9	109	2149	3.41	<10	0.80	828	12	0.01	5	870	32	5	<20	237	0.02	<10	10	<10	2	61
15	G35992	2.6	0.61	<5	50	<5	0.96	2	11	119	2809	3.59	<10	0.53	635	10	0.01	6	720	48	5	<20	31	0.01	<10	8	<10	2	79
16	G35993	3.8	1.23	<5	55	<5	0.54	2	14	89	4085	4.02	<10	0.97	489	50	0.01	5	930	30	10	<20	21	0.01	<10	14	<10	2	117
17	G35994	5.6	0.31	<5	35	<5	1.31	19	9	157	2082	3.02	<10	0.35	949	15	0.01	6	510	138	20	<20	43	0.01	<10	6	<10	<1	549
18	G35995	11.7	0.25	25	35	<5	1.23	5	10	125	1627	3.38	<10	0.46	800	12	0.01	5	680	42	75	<20	63	0.02	<10	5	<10	1	161
19	G35996	1.0	0.24	<5	50	<5	3.28	1	13	125	135	5.04	<10	1.50	1719	43	0.02	4	180	8	10	<20	56	0.04	<10	5	<10	<1	11
20	G35997	3.9	1.12	40	60	<5	1.01	2	22	58	8698	4.01	20	0.64	199	593	0.04	59	30	66	20	<20	64	0.04	<10	44	<10	7	65
21	G35998	1.9	0.21	<5	35	<5	2.99	2	10	131	721	4.76	<10	1.13	1668	20	0.02	5	350	18	10	<20	139	0.03	<10	4	<10	<1	25
22	G35999	2.3	0.29	<5	50	<5	0.46	2	18	146	995	5.17	<10	0.14	258	22	0.01	8	720	20	25	<20	19	0.01	<10	5	<10	<1	22
23	G36000	1.6	0.30	<5	50	<5	0.69	2	11	124	1393	3.72	<10	0.35	426	14	0.01	6	720	24	10	<20	21	0.01	<10	4	<10	<1	36
24	X05001	2.4	0.33	<5	45	<5	0.23	2	18	168	1717	4.29	<10	0.12	124	17	0.01	6	560	28	10	<20	12	0.01	<10	5	<10	<1	25
25	X05002	0.3	0.20	<5	55	45	0.11	5	59	116	88	8.06	<10	<0.01	41	123	0.01	5	240	14	<5	<20	11	0.03	<10	3	<10	<1	165

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05003	0.3	0.28	<5	50	5	0.13	1	19	138	207	4.96	<10	<0.01	30	73	0.01	5	500	14	<5	<20	14	0.02	<10	5	<10	<1	2
27	X05004	1.7	0.34	<5	50	<5	0.21	<1	8	109	1479	2.90	<10	0.11	66	15	0.01	3	780	14	<5	<20	15	<0.01	<10	4	<10	<1	16
28	X05005	1.7	0.27	<5	45	<5	0.20	1	14	162	657	5.47	<10	<0.01	73	31	0.01	6	510	22	<5	<20	48	0.02	<10	5	<10	<1	7
29	X05006	0.4	0.25	<5	50	30	0.09	2	16	143	93	5.49	<10	<0.01	23	48	0.01	7	410	14	<5	<20	7	0.02	<10	5	<10	<1	40
30	X05007	3.1	0.36	20	45	<5	0.23	1	8	176	1931	3.43	<10	0.03	78	15	0.02	7	870	24	15	<20	11	0.01	<10	6	<10	<1	17
31	X05008	2.8	0.25	10	40	<5	0.22	2	14	169	1557	4.59	<10	0.02	125	12	0.01	6	580	16	30	<20	17	0.01	<10	5	<10	<1	17
32	X05009	3.1	0.30	20	45	<5	0.20	2	10	137	1401	3.21	<10	0.02	79	18	0.01	6	570	16	20	<20	11	<0.01	<10	5	<10	<1	38
33	X05010	4.4	0.30	25	35	<5	0.26	2	7	133	2713	2.89	<10	0.08	64	11	0.01	6	880	20	40	<20	12	<0.01	<10	5	<10	<1	47
34	X05011	2.0	0.34	10	40	<5	0.49	2	7	103	2061	3.35	<10	0.23	375	9	0.01	4	870	34	10	<20	18	0.01	<10	6	<10	<1	73
35	X05012	3.7	0.33	<5	45	<5	0.17	3	14	163	4028	5.06	<10	0.07	95	18	0.01	7	290	44	<5	<20	12	<0.01	<10	6	<10	<1	132
QC DATA:																													
Repeat:																													
1	G35978	1.8	0.54	<5	55	<5	0.40	2	11	97	1182	3.35	<10	0.28	183	38	0.02	5	1050	20	<5	<20	24	0.01	<10	7	<10	2	44
10	G35987	1.6	0.80	<5	60	<5	1.71	2	9	94	1803	3.21	<10	1.01	902	17	0.01	4	830	28	5	<20	48	0.02	<10	12	<10	2	66
19	G35996	1.0	0.25	<5	50	25	3.31	1	14	126	132	5.06	<10	1.49	1730	43	0.01	6	200	10	10	<20	59	0.03	<10	6	<10	<1	11
Resplit:																													
1	G35978	2.0	0.54	<5	40	<5	0.57	1	12	104	1172	3.66	<10	0.31	202	40	0.02	5	1070	22	<5	<20	26	0.01	<10	8	<10	2	48
Standard:																													
PB113A		11.7	0.26	45	65	<5	1.69	38	3	6	2292	1.04	<10	0.11	1417	69	0.02	2	80	5576	20	<20	82	0.02	<10	8	<10	<1	6998

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
dl/5632
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5633

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

7-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07144
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09517	0.57	0.017
2	X09518	0.39	0.011
3	X09519	0.67	0.020
4	X09520	0.52	0.015
5	X09521	0.48	0.014
6	X09522	1.92	0.056
7	X09523	0.48	0.014
8	X09524	0.45	0.013
9	X09525	0.45	0.013
10	X09526	0.51	0.015
11	X09527	0.73	0.021
12	X09528	0.85	0.025
13	X09529	0.73	0.021
14	X09530	0.63	0.018
15	X09531	0.53	0.015
16	X09532	0.97	0.028
17	X09533	0.97	0.028
18	X09534	0.96	0.028
19	X09535	1.09	0.032
20	X09536	1.41	0.041
21	X09537	1.08	0.031
22	X09538	1.09	0.032
23	X09539	1.29	0.038
24	X09540	1.09	0.032
25	X09541	0.89	0.026

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AK7-5633 7-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X09542	0.98	0.029
27	X09543	0.91	0.027
28	X09544	0.65	0.019
29	X09545	<0.03	<0.001
30	X09546	0.87	0.025
31	X09547	0.87	0.025
32	X09548	0.69	0.020
33	X09549	0.64	0.019
34	X09550	0.60	0.017
35	X09551	1.01	0.029
QC DATA:			
Repeat:			
1	X09517	0.56	0.016
3	X09519	0.58	0.017
4	X09520	0.72	0.021
10	X09526	0.59	0.017
16	X09532	0.90	0.026
19	X09535	1.08	0.031
20	X09536	1.40	0.041
Resplits:			
1	X09517	0.67	0.020
Standard:			
OXi54		1.86	0.054

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

14-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5633

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07144
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09517	1.8	0.25	<5	35	<5	0.14	3	10	151	1473	4.05	<10	0.02	55	59	0.01	6	550	82	<5	<20	12	0.01	<10	7	<10	<1	74
2	X09518	1.5	0.23	5	30	<5	0.11	1	8	183	1151	3.51	<10	<0.01	36	37	0.01	5	430	62	<5	<20	12	<0.01	<10	7	<10	<1	23
3	X09519	1.9	0.30	<5	35	<5	0.16	2	10	168	1196	4.14	<10	0.06	71	69	<0.01	5	650	30	<5	<20	13	0.01	<10	8	<10	<1	83
4	X09520	1.8	0.25	5	40	<5	0.16	1	11	183	1192	4.10	<10	<0.01	40	51	0.01	7	630	30	<5	<20	14	0.01	<10	8	<10	<1	22
5	X09521	3.0	0.24	15	35	<5	0.12	1	10	193	1447	3.86	<10	0.01	61	65	<0.01	7	440	48	<5	<20	24	0.01	<10	7	<10	<1	29
6	X09522	4.0	1.17	35	50	<5	1.01	2	22	61	8574	4.08	20	0.62	198	651	0.04	64	110	70	25	<20	58	0.04	<10	45	<10	6	66
7	X09523	6.1	0.22	95	30	<5	0.15	3	10	160	1467	3.68	<10	<0.01	42	140	<0.01	6	590	134	25	<20	21	<0.01	<10	7	<10	<1	112
8	X09524	7.3	0.21	50	25	<5	0.10	2	11	194	1484	4.14	<10	<0.01	41	91	0.01	9	220	40	15	<20	8	0.02	<10	6	<10	<1	39
9	X09525	4.8	0.46	<5	25	<5	0.15	1	8	189	1344	3.40	<10	0.23	162	75	0.01	6	360	30	<5	<20	12	0.03	<10	7	<10	<1	35
10	X09526	6.9	0.22	<5	30	<5	0.14	1	11	173	1445	3.70	<10	<0.01	39	81	0.01	5	330	52	<5	<20	13	0.02	<10	5	<10	<1	25
11	X09527	6.5	0.56	<5	30	<5	0.23	1	10	136	1849	3.95	<10	0.44	315	63	0.01	6	320	22	<5	<20	16	0.03	<10	10	<10	<1	53
12	X09528	2.8	0.78	<5	35	<5	0.15	<1	9	181	1922	3.79	<10	0.55	234	114	0.01	6	340	18	<5	<20	14	0.03	<10	11	<10	<1	31
13	X09529	3.0	0.62	<5	25	<5	0.19	1	11	172	2170	3.62	<10	0.42	283	163	0.01	5	260	20	<5	<20	13	0.03	<10	10	<10	<1	28
14	X09530	2.7	0.32	<5	20	<5	0.17	<1	10	220	2441	3.34	<10	0.06	72	78	0.01	7	370	24	<5	<20	15	0.03	<10	9	<10	<1	14
15	X09531	3.1	0.29	<5	25	<5	0.19	3	11	195	1635	3.51	<10	0.03	88	142	0.01	7	450	114	<5	<20	20	0.03	<10	8	<10	<1	80
16	X09532	5.4	0.77	<5	30	<5	0.66	2	12	185	2419	3.95	<10	0.75	841	130	0.01	6	510	22	<5	<20	34	0.04	<10	19	<10	<1	26
17	X09533	7.9	0.42	10	25	<5	0.29	<1	8	158	3455	2.62	<10	0.24	225	155	0.01	6	390	20	5	<20	24	0.03	<10	13	<10	1	18
18	X09534	8.1	0.38	10	25	<5	0.27	<1	9	158	3362	2.88	<10	0.24	223	125	0.01	5	340	22	5	<20	23	0.03	<10	12	<10	<1	19
19	X09535	3.2	0.81	<5	25	<5	0.40	<1	12	145	2229	3.40	<10	0.75	355	115	0.01	7	580	16	<5	<20	34	0.03	<10	20	<10	<1	29
20	X09536	2.6	0.74	<5	25	<5	0.43	1	13	150	3142	3.58	<10	0.70	377	108	0.01	6	470	26	<5	<20	42	0.03	<10	21	<10	<1	33
21	X09537	1.9	0.71	<5	30	<5	0.50	2	14	124	2279	4.39	<10	0.68	401	82	0.01	6	540	38	<5	<20	35	0.04	<10	20	<10	<1	29
22	X09538	2.3	0.54	<5	30	<5	0.53	1	10	164	2600	3.50	<10	0.50	407	132	0.01	6	400	34	<5	<20	31	0.03	<10	15	<10	<1	30
23	X09539	1.8	0.79	<5	30	<5	0.72	1	12	161	2592	4.22	<10	0.74	539	94	0.01	7	540	18	<5	<20	47	0.04	<10	22	<10	<1	24
24	X09540	2.3	0.97	<5	35	<5	0.56	2	12	138	1983	3.91	<10	0.91	452	103	0.01	6	660	26	<5	<20	36	0.04	<10	25	<10	2	51
25	X09541	3.3	0.77	<5	20	<5	0.66	1	11	179	2092	3.15	<10	0.74	523	68	0.01	7	560	22	<5	<20	37	0.03	<10	21	<10	2	18

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09542	2.0	0.95	<5	30	<5	0.64	1	10	130	1865	3.23	<10	0.94	516	133	0.01	6	660	22	<5	<20	40	0.03	<10	26	<10	2	30
27	X09543	6.8	0.73	<5	30	<5	0.45	1	11	160	2441	4.20	<10	0.64	398	82	0.01	7	590	18	<5	<20	25	0.04	<10	21	<10	1	29
28	X09544	8.2	0.45	5	25	<5	0.53	1	11	156	2176	4.06	<10	0.34	445	108	0.01	6	670	24	<5	<20	29	0.04	<10	16	<10	1	22
29	X09545	<0.2	1.05	<5	250	10	0.62	<1	7	108	7	2.14	<10	0.61	529	4	0.14	7	680	12	5	<20	98	0.14	<10	47	<10	6	40
30	X09546	7.6	0.60	<5	25	<5	0.52	25	9	151	2238	3.37	<10	0.50	485	100	0.01	7	540	298	<5	<20	35	0.03	<10	18	<10	<1	1579
31	X09547	4.4	0.71	<5	25	<5	0.58	1	12	181	2269	3.50	<10	0.61	492	234	0.01	7	710	18	<5	<20	40	0.04	<10	22	<10	2	41
32	X09548	9.4	0.56	60	25	<5	0.30	8	10	164	2234	4.19	<10	0.40	298	431	0.01	6	540	190	25	<20	19	0.04	<10	18	<10	<1	561
33	X09549	12.6	0.34	50	30	<5	0.31	19	12	149	2013	4.25	<10	0.14	274	163	0.01	6	520	294	25	<20	25	0.03	<10	11	<10	<1	1286
34	X09550	9.2	0.38	<5	25	<5	0.39	23	12	139	1883	4.21	<10	0.18	351	99	0.01	7	710	462	<5	<20	26	0.03	<10	14	<10	<1	1561
35	X09551	3.2	0.93	<5	25	<5	0.55	1	11	124	1833	4.07	<10	0.91	505	79	0.01	6	810	22	<5	<20	39	0.04	<10	27	<10	2	65
QC DATA:																													
Repeat:																													
1	X09517	1.6	0.26	<5	30	<5	0.14	3	9	156	1487	4.07	<10	0.02	51	61	0.01	5	350	76	<5	<20	9	0.03	<10	6	<10	<1	72
10	X09526	6.8	0.23	<5	25	<5	0.14	2	11	178	1496	3.72	<10	<0.01	40	86	0.01	8	330	50	5	<20	11	0.02	<10	5	<10	<1	24
19	X09535	3.4	0.82	5	25	<5	0.40	<1	12	149	2230	3.44	<10	0.75	357	117	0.01	6	590	18	<5	<20	36	0.03	<10	21	<10	1	30
Resplit:																													
1	X09517	1.8	0.27	<5	30	<5	0.12	3	10	178	1341	4.00	<10	0.02	59	64	0.01	7	300	96	<5	<20	8	0.03	<10	6	<10	<1	68
Standard:																													
PB113A		11.9	0.27	45	50	<5	1.65	39	2	5	2250	1.03	<10	0.10	1392	75	0.02	2	<10	5580	15	<20	86	0.03	<10	8	<10	<1	6941

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5632
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5634

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

7-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07145
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05013	0.26	0.008
2	X05014	0.25	0.007
3	X05015	0.69	0.020
4	X05016	0.73	0.021
5	X05017	0.46	0.013
6	X05018	0.50	0.015
7	X05019	0.41	0.012
8	X05020	0.27	0.008
9	X05021	0.76	0.022
10	X05022	0.66	0.019
11	X05023	0.41	0.012
12	X05024	0.45	0.013
13	X05025	0.59	0.017
14	X05026	<0.03	<0.001
15	X05027	0.15	0.004
16	X05028	0.24	0.007
17	X05029	0.26	0.008
18	X05030	0.48	0.014
19	X05031	0.25	0.007
20	X05032	0.57	0.017
21	X05033	1.00	0.029
22	X05034	0.72	0.021
23	X05035	0.76	0.022
24	X05036	0.67	0.020
25	X05037	0.96	0.028

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AK7-5634 7-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X05038	0.91	0.027
27	X05039	0.38	0.011
28	X05040	0.31	0.009
29	X05041	0.43	0.013
30	X05042	0.21	0.006
31	X05043	0.77	0.022
32	X05044	0.52	0.015
33	X05045	0.75	0.022
34	X05046	0.43	0.013
35	X05047	0.79	0.023

QC DATA:

Repeat:

1	X05013	0.24	0.007
10	X05022	0.68	0.020
19	X05031	0.23	0.007
21	X05033	0.93	0.027
26	X05038	1.01	0.029
35	X05047	0.67	0.020

Resplits:

1	X05013	0.28	0.008

Standard:

OXi54		1.82	0.053

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

14-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5634

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07145
Submitted by: Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05013	2.6	0.30	<5	30	<5	0.36	2	9	114	3568	3.42	<10	0.15	172	7	0.01	5	410	30	<5	<20	11	0.03	<10	5	<10	<1	92
2	X05014	2.4	0.39	<5	30	<5	1.06	2	9	132	4218	4.11	<10	0.48	428	12	0.01	5	330	32	<5	<20	26	0.04	<10	7	<10	<1	57
3	X05015	2.8	0.32	<5	35	<5	0.97	2	8	157	3738	4.13	<10	0.39	549	11	0.01	6	200	26	<5	<20	22	0.03	<10	8	<10	<1	32
4	X05016	6.3	0.34	15	30	<5	0.72	2	8	180	4206	3.59	<10	0.28	440	9	0.01	7	120	30	40	<20	18	0.03	<10	7	<10	<1	42
5	X05017	2.4	0.31	<5	25	<5	0.65	1	8	178	3107	4.04	<10	0.26	495	13	0.01	6	270	18	<5	<20	20	0.03	<10	7	<10	<1	16
6	X05018	1.4	0.36	<5	25	<5	1.02	1	7	161	2138	3.48	<10	0.43	412	7	0.02	5	350	20	<5	<20	33	0.03	<10	8	<10	<1	31
7	X05019	1.6	0.37	<5	25	<5	1.68	3	9	113	1993	4.83	<10	0.27	407	9	0.01	6	650	30	<5	<20	160	0.04	<10	8	<10	<1	94
8	X05020	2.2	0.26	15	20	<5	1.89	2	10	151	2070	4.06	<10	0.15	380	10	0.01	6	460	34	<5	<20	103	0.03	<10	5	<10	<1	62
9	X05021	1.1	0.41	<5	25	<5	0.87	1	8	119	1124	3.40	<10	0.25	332	13	0.01	5	860	14	<5	<20	20	0.03	<10	9	<10	1	26
10	X05022	0.9	0.44	<5	25	<5	1.01	<1	8	100	975	3.26	<10	0.29	383	10	0.01	4	820	12	<5	<20	19	0.03	<10	9	<10	1	30
11	X05023	1.0	0.43	<5	30	<5	1.99	1	8	112	877	3.38	<10	0.37	814	9	0.01	5	830	12	<5	<20	45	0.03	<10	9	<10	4	27
12	X05024	2.0	0.25	<5	25	<5	1.19	2	9	163	2462	3.26	<10	0.10	398	13	0.01	6	400	28	<5	<20	50	0.03	<10	5	<10	<1	42
13	X05025	2.4	0.33	<5	25	<5	0.85	1	8	127	2963	3.37	<10	0.25	379	10	0.01	4	440	24	<5	<20	34	0.03	<10	6	<10	<1	27
14	X05026	<0.2	0.99	<5	240	10	0.60	<1	7	104	7	2.17	<10	0.58	528	1	0.13	5	710	14	<5	<20	90	0.14	<10	46	<10	5	43
15	X05027	2.7	0.24	5	25	<5	1.55	2	10	137	1853	3.67	<10	0.23	366	12	0.01	5	480	34	10	<20	98	0.03	<10	5	<10	<1	33
16	X05028	2.0	0.18	<5	25	<5	1.28	2	14	152	2167	4.19	<10	0.10	299	34	0.01	5	150	22	<5	<20	99	0.04	<10	5	<10	<1	14
17	X05029	2.4	0.24	<5	25	<5	1.01	2	12	171	2019	3.49	<10	0.20	421	14	0.01	5	290	38	10	<20	47	0.03	<10	5	<10	<1	42
18	X05030	2.2	0.24	<5	20	<5	2.48	1	8	171	3819	3.52	<10	0.40	415	10	0.02	5	220	26	<5	<20	189	0.04	<10	7	<10	<1	29
19	X05031	4.3	0.23	<5	25	<5	1.37	2	12	132	3367	4.22	<10	0.27	531	14	0.01	6	250	54	<5	<20	75	0.04	<10	7	<10	<1	57
20	X05032	7.3	0.21	<5	30	<5	0.19	3	12	147	3173	5.20	<10	<0.01	70	15	0.01	6	160	140	5	<20	12	0.04	<10	5	<10	<1	89
21	X05033	2.6	0.47	<5	25	<5	1.43	1	8	145	2554	2.65	<10	0.46	505	9	0.01	6	460	22	<5	<20	81	0.03	<10	9	<10	1	44
22	X05034	2.3	0.44	<5	20	<5	2.60	1	6	154	2543	2.64	<10	0.42	679	11	0.02	5	400	30	<5	<20	161	0.03	<10	9	<10	<1	51
23	X05035	3.2	0.29	<5	25	<5	1.58	2	10	131	4428	3.47	<10	0.19	440	7	0.01	5	140	32	<5	<20	89	0.04	<10	9	<10	<1	35
24	X05036	1.5	0.57	<5	25	<5	2.35	2	8	156	1833	3.56	<10	0.51	569	10	0.02	7	430	28	<5	<20	181	0.03	<10	14	<10	<1	36
25	X05037	2.1	0.41	<5	25	<5	1.63	1	11	151	2431	3.65	<10	0.43	536	11	0.02	5	390	46	<5	<20	88	0.04	<10	8	<10	<1	39

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05038	1.8	0.57	<5	25	<5	1.20	2	15	134	2316	3.75	<10	0.37	383	12	0.01	7	420	30	<5	<20	56	0.03	<10	11	<10	<1	43
27	X05039	2.1	0.26	<5	25	<5	0.62	1	10	144	2272	3.59	<10	0.09	243	15	0.01	5	300	28	<5	<20	25	0.03	<10	6	<10	<1	31
28	X05040	3.2	1.20	15	40	<5	0.96	3	21	60	2679	3.46	20	0.61	190	213	0.04	10	290	62	10	<20	55	0.06	<10	47	<10	7	268
29	X05041	1.9	0.28	<5	15	<5	2.56	2	8	143	3167	3.17	<10	0.28	535	10	0.01	6	240	38	<5	<20	200	0.03	<10	6	<10	<1	47
30	X05042	1.4	0.33	<5	20	<5	1.51	2	6	160	1958	2.71	<10	0.37	631	7	0.01	5	440	48	<5	<20	60	0.03	<10	8	<10	<1	49
31	X05043	1.8	0.44	<5	20	<5	1.76	2	7	190	2383	2.89	<10	0.40	654	11	0.01	7	320	32	<5	<20	60	0.03	<10	10	<10	<1	58
32	X05044	1.6	0.34	<5	25	<5	1.62	1	6	124	2259	2.57	<10	0.34	703	9	0.01	5	480	30	<5	<20	46	0.03	<10	7	<10	2	34
33	X05045	2.1	0.35	<5	30	<5	0.75	1	11	126	2856	3.53	<10	0.23	427	37	0.01	5	300	20	<5	<20	33	0.03	<10	8	<10	<1	25
34	X05046	5.9	0.26	15	30	<5	0.40	3	10	160	5015	4.05	<10	0.07	248	9	0.01	4	200	52	20	<20	16	0.04	<10	5	<10	<1	103
35	X05047	2.7	0.35	<5	25	<5	0.21	2	9	117	2322	3.42	<10	0.11	49	12	0.01	5	550	26	<5	<20	7	0.03	<10	7	<10	<1	53
QC DATA:																													
Repeat:																													
1	X05013	2.6	0.31	<5	25	<5	0.36	2	9	116	3602	3.48	<10	0.15	175	6	0.01	5	420	30	<5	<20	11	0.02	<10	5	<10	<1	94
10	X05022	1.0	0.45	<5	25	<5	1.02	<1	8	101	984	3.26	<10	0.29	382	10	0.01	4	810	14	<5	<20	24	0.03	<10	10	<10	2	30
19	X05031	4.3	0.24	<5	25	<5	1.38	3	12	133	3404	4.26	<10	0.27	536	15	0.01	6	250	52	<5	<20	77	0.04	<10	7	<10	<1	60
Resplit:																													
1	X05013	3.1	0.35	<5	35	<5	0.38	3	8	164	3745	3.32	<10	0.16	190	7	0.01	5	430	30	<5	<20	15	0.03	<10	6	<10	<1	109
Standard:																													
PB113A		11.6	0.28	65	45	<5	1.69	41	2	5	2271	1.06	<10	0.11	1436	68	0.02	2	<10	5578	20	<20	83	0.03	<10	8	<10	<1	6970

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
dl/5634
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5635

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

7-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07146
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05048	0.37	0.011
2	X05049	0.41	0.012
3	X05050	0.56	0.016
4	X05051	0.80	0.023
5	X05052	0.45	0.013
6	X05053	0.84	0.024
7	X05054	0.70	0.020
8	X05055	0.48	0.014
9	X05056	0.50	0.015
10	X05057	1.01	0.029
11	X05058	0.84	0.024
12	X05059	0.57	0.017
13	X05060	0.57	0.017
14	X05061	1.03	0.030
15	X05062	0.73	0.021
16	X05063	0.56	0.016
17	X05064	0.51	0.015
18	X05065	0.53	0.015
19	X05066	0.60	0.017
20	X05067	0.66	0.019
21	X05068	0.31	0.009
22	X05069	0.42	0.012
23	X05070	0.79	0.023
24	X05071	0.54	0.016
25	X05072	0.41	0.012

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AK7-5635

7-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X05073	<0.03	<0.001
27	X05074	0.37	0.011
28	X05075	0.59	0.017
29	X05076	0.73	0.021
30	X05077	0.46	0.013
31	X05078	0.46	0.013
32	X05079	0.46	0.013
33	X05080	0.44	0.013
34	X05081	0.56	0.016
35	X05082	0.58	0.017

QC DATA:

Repeat:

1	X05048	0.37	0.011
10	X05057	0.98	0.029
19	X05066	0.62	0.018

Resplits:

1	X05048	0.30	0.009

Standard:

OXi54		1.84	0.054

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

16-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5635

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07146
Submitted by: Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05048	4.2	0.24	<5	20	<5	0.10	2	8	196	2398	2.95	<10	0.05	44	7	0.01	6	170	36	<5	<20	14	0.03	<10	5	<10	<1	67
2	X05049	6.9	0.18	<5	30	<5	0.10	3	10	195	5696	3.92	<10	<0.01	42	15	0.01	7	<10	48	<5	<20	5	0.04	<10	4	<10	<1	119
3	X05050	15.3	0.21	5	20	<5	0.11	2	9	173	1577	3.61	<10	<0.01	33	11	0.01	10	270	52	5	<20	16	0.03	<10	6	<10	<1	70
4	X05051	7.6	0.39	<5	30	<5	1.17	2	7	154	2149	2.75	<10	0.24	625	8	0.01	5	520	34	<5	<20	30	0.03	<10	5	<10	3	74
5	X05052	4.2	0.23	<5	30	<5	0.31	2	12	166	2716	4.72	<10	<0.01	133	16	0.01	6	340	62	<5	<20	12	0.04	<10	4	<10	<1	66
6	X05053	1.5	0.95	<5	30	<5	1.07	<1	6	160	1351	2.81	<10	0.85	648	12	0.02	5	560	14	<5	<20	51	0.03	<10	13	<10	1	77
7	X05054	2.2	0.80	<5	20	<5	1.43	1	7	146	1987	2.94	<10	0.68	619	11	0.02	5	470	16	<5	<20	103	0.03	<10	11	<10	<1	64
8	X05055	2.1	0.53	<5	35	<5	0.41	2	7	150	1668	2.92	<10	0.33	238	10	0.01	6	520	38	<5	<20	12	0.03	<10	7	<10	1	73
9	X05056	2.1	1.11	<5	25	<5	2.58	1	6	155	1402	3.07	<10	0.82	743	12	0.04	6	610	18	<5	<20	197	0.03	<10	31	<10	2	89
10	X05057	2.9	0.89	<5	30	<5	1.95	<1	7	137	2418	2.77	<10	0.66	613	9	0.02	5	500	20	<5	<20	119	0.03	<10	16	<10	1	72
11	X05058	2.8	0.41	<5	25	<5	1.65	2	9	148	3325	3.09	<10	0.29	582	24	0.02	6	380	46	<5	<20	93	0.03	<10	9	<10	1	60
12	X05059	2.2	0.31	<5	20	<5	2.07	3	9	173	3151	3.08	<10	0.16	685	9	0.02	6	220	76	<5	<20	115	0.03	<10	7	<10	<1	113
13	X05060	1.6	0.42	<5	25	<5	0.55	2	9	163	2551	3.08	<10	0.24	413	11	0.01	5	350	62	<5	<20	13	0.03	<10	9	<10	<1	122
14	X05061	3.7	1.13	55	45	<5	0.73	3	17	59	3264	3.94	20	0.50	270	222	0.04	13	220	136	30	<20	34	0.06	<10	44	<10	6	156
15	X05062	2.9	0.53	<5	25	<5	0.36	4	7	130	2902	3.07	<10	0.29	233	10	0.01	4	400	42	<5	<20	8	0.03	<10	7	<10	<1	242
16	X05063	2.2	0.17	<5	25	<5	0.34	4	11	203	3673	2.83	<10	<0.01	162	15	0.01	6	<10	108	<5	<20	8	0.03	<10	5	<10	<1	190
17	X05064	<0.2	0.35	<5	20	<5	1.19	2	8	196	2674	3.12	<10	0.18	480	6	0.02	6	210	48	<5	<20	48	0.04	<10	8	<10	<1	53
18	X05065	2.5	0.44	<5	20	<5	1.24	4	9	148	2479	3.47	<10	0.24	370	11	0.02	5	340	74	<5	<20	85	0.04	<10	12	<10	<1	151
19	X05066	3.0	0.20	<5	20	<5	1.31	3	13	167	3109	3.53	<10	<0.01	368	11	0.02	6	120	48	<5	<20	77	0.03	<10	6	<10	<1	82
20	X05067	2.6	0.23	<5	25	<5	1.90	2	10	190	3432	4.06	<10	0.04	554	10	0.02	6	160	50	<5	<20	120	0.04	<10	7	<10	<1	50
21	X05068	2.3	0.16	<5	25	<5	0.24	4	11	212	1856	4.37	<10	<0.01	110	9	0.01	7	30	90	<5	<20	17	0.04	<10	9	<10	<1	189
22	X05069	1.7	0.49	<5	30	<5	1.02	2	6	227	1663	2.44	<10	0.35	365	13	0.04	7	270	38	<5	<20	30	0.02	<10	14	<10	<1	101
23	X05070	1.9	0.61	<5	30	<5	1.11	1	8	171	1887	2.67	<10	0.43	463	12	0.02	5	340	30	<5	<20	30	0.03	<10	12	<10	<1	82
24	X05071	2.8	0.30	<5	25	<5	0.23	4	11	175	2228	3.84	<10	0.08	82	8	0.01	6	340	98	<5	<20	10	0.03	<10	6	<10	<1	178
25	X05072	2.2	0.22	<5	20	<5	2.23	2	7	230	2560	2.69	<10	0.04	472	11	0.02	7	270	32	<5	<20	165	0.03	<10	6	<10	<1	45

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05073	<0.2	1.06	<5	250	10	0.64	<1	7	124	8	2.29	<10	0.60	555	2	0.13	6	710	16	<5	<20	103	0.14	<10	49	<10	6	44
27	X05074	2.6	0.19	<5	20	<5	1.85	18	11	176	2679	3.17	<10	0.07	368	27	0.02	6	210	56	<5	<20	164	0.03	<10	6	<10	<1	935
28	X05075	1.9	0.47	<5	25	<5	2.64	2	9	160	1775	3.32	<10	0.32	490	12	0.02	6	430	22	<5	<20	234	0.03	<10	13	<10	<1	51
29	X05076	4.2	0.44	<5	20	<5	1.73	2	9	187	2108	3.34	<10	0.24	358	10	0.02	6	390	40	<5	<20	143	0.03	<10	10	<10	<1	104
30	X05077	4.9	0.23	10	30	<5	0.62	3	14	130	2577	5.77	<10	<0.01	232	15	0.01	6	370	48	<5	<20	21	0.05	<10	9	<10	<1	50
31	X05078	3.0	0.22	<5	25	<5	1.31	2	10	149	3080	4.34	<10	<0.01	464	15	0.01	6	350	62	<5	<20	32	0.04	<10	8	<10	<1	56
32	X05079	4.0	0.21	10	25	<5	0.51	2	13	176	3693	4.43	<10	<0.01	207	28	0.01	6	230	78	<5	<20	15	0.04	<10	7	<10	<1	80
33	X05080	3.4	0.23	<5	30	<5	2.14	5	15	163	2600	5.19	<10	0.34	892	11	0.02	8	400	122	<5	<20	101	0.05	<10	7	<10	<1	149
34	X05081	2.2	0.43	<5	15	<5	2.97	2	8	159	2133	3.53	<10	0.35	620	11	0.02	5	490	20	<5	<20	247	0.04	<10	12	<10	1	61
35	X05082	3.2	0.46	<5	20	<5	1.64	1	11	159	3327	3.57	<10	0.24	490	10	0.02	4	400	24	<5	<20	81	0.04	<10	12	<10	1	32
QC DATA:																													
Repeat:																													
1	X05048	4.5	0.25	<5	20	<5	0.10	2	8	195	2400	2.96	<10	0.05	47	7	0.01	5	150	36	<5	<20	11	0.03	<10	6	<10	<1	67
10	X05057	2.8	0.92	<5	30	<5	1.97	<1	8	139	2492	2.81	<10	0.68	624	7	0.02	5	510	20	<5	<20	122	0.03	<10	16	<10	1	72
19	X05066	3.1	0.20	<5	20	<5	1.30	3	13	163	3076	3.49	<10	<0.01	361	12	0.02	5	130	48	<5	<20	76	0.04	<10	6	<10	<1	83
Resplit:																													
1	X05048	4.4	0.23	<5	20	<5	0.10	2	7	182	2452	2.74	<10	0.04	44	6	0.01	6	140	36	<5	<20	11	0.02	<10	5	<10	<1	62
Standard:																													
Pb113A		11.2	0.28	40	50	<5	1.63	42	3	5	2263	1.09	<10	0.11	1479	68	0.02	2	<10	5548	15	<20	89	0.03	<10	8	<10	<1	6933

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5632
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5636

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

14-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07147
Submitted by: Peter Erwick

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09552	0.94	0.027
2	X09553	1.11	0.032
3	X09554	0.72	0.021
4	X09555	0.80	0.023
5	X09556	0.76	0.022
6	X09557	0.95	0.028
7	X09558	0.99	0.029
8	X09559	0.82	0.024
9	X09560	0.92	0.027
10	X09561	1.08	0.031
11	X09562	0.89	0.026
12	X09563	0.80	0.023
13	X09564	0.79	0.023
14	X09565	0.59	0.017
15	X09566	0.84	0.024
16	X09567	0.73	0.021
17	X09568	0.46	0.013
18	X09569	0.57	0.017
19	X09570	0.48	0.014
20	X09571	0.47	0.014
21	X09572	<0.03	<0.001
22	X09573	0.29	0.008
23	X09574	1.06	0.031
24	X09575	0.43	0.013
25	X09576	0.66	0.019

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5636 14-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X09577	0.59	0.017
27	X09578	0.40	0.012
28	X09579	0.62	0.018
29	X09580	0.53	0.015
30	X09581	0.93	0.027
31	X09582	0.60	0.017
32	X09583	0.64	0.019
33	X09584	0.07	0.002
34	X09585	0.42	0.012
35	X09586	0.65	0.019

QC DATA:

Repeat:

1	X09552	0.99	0.029
2	X09553	1.20	0.035
9	X09560	0.96	0.028
10	X09561	1.00	0.029
19	X09570	0.44	0.013
23	X09574	1.01	0.029
32	X09583	0.66	0.019

Resplits:

1	X09552	1.05	0.031

Standard:

OXi54		1.84	0.054

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
XLS/07

15-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5636
Revised

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07147
Submitted by: Peter Erwick

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09552	3.9	0.84	15	30	<5	0.64	1	10	160	1893	3.92	<10	0.82	699	86	0.02	5	1220	22	<5	<20	42	<0.01	<10	18	<10	4	52
2	X09553	4.5	0.64	15	30	<5	0.59	1	8	120	2269	3.71	<10	0.62	582	110	0.02	4	1280	26	<5	<20	39	<0.01	<10	15	<10	4	45
3	X09554	3.6	0.66	15	30	<5	0.45	1	11	157	2059	4.52	<10	0.53	347	126	0.02	5	1280	16	<5	<20	32	<0.01	<10	16	<10	4	34
4	X09555	3.1	0.95	20	30	<5	0.63	2	11	129	1751	4.10	<10	0.88	518	55	0.02	4	1470	14	<5	<20	39	<0.01	<10	23	<10	4	62
5	X09556	2.7	1.09	10	40	<5	1.28	1	10	142	1748	3.65	<10	0.97	711	46	0.02	5	1130	6	<5	<20	99	<0.01	<10	27	<10	4	44
6	X09557	3.6	1.26	20	35	<5	1.04	1	11	170	1787	4.14	<10	1.26	814	68	0.02	5	1240	6	<5	<20	69	<0.01	<10	26	<10	5	60
7	X09558	5.3	0.91	20	35	<5	0.80	1	11	136	2507	3.77	<10	0.92	697	125	0.02	4	1130	10	<5	<20	45	<0.01	<10	19	<10	4	45
8	X09559	10.8	0.95	40	45	<5	1.26	2	19	147	2531	5.15	<10	1.13	1206	73	0.02	5	1290	26	<5	<20	70	<0.01	<10	21	<10	5	59
9	X09560	7.8	0.91	15	40	<5	0.96	2	9	156	2416	4.75	<10	1.05	961	53	0.02	4	1140	16	<5	<20	54	<0.01	<10	19	<10	4	44
10	X09561	3.2	1.27	15	40	<5	1.39	2	11	131	2376	4.36	<10	1.23	1008	65	0.02	4	1200	10	<5	<20	98	<0.01	<10	23	<10	5	70
11	X09562	2.0	1.82	25	85	<5	1.48	2	10	136	1416	4.33	<10	1.76	1176	36	0.02	5	1270	6	<5	<20	100	<0.01	<10	29	<10	4	78
12	X09563	2.4	1.14	25	45	<5	0.94	5	8	131	1364	3.67	<10	1.10	876	85	0.02	4	1300	204	<5	<20	60	<0.01	<10	22	<10	5	144
13	X09564	2.9	1.03	25	40	<5	1.00	5	9	148	1466	3.63	<10	0.91	815	66	0.02	5	1420	220	<5	<20	60	<0.01	<10	21	<10	5	157
14	X09565	2.8	1.08	25	35	<5	0.93	1	9	134	1284	3.93	<10	1.02	790	39	0.02	4	1490	40	<5	<20	58	<0.01	<10	22	<10	5	64
15	X09566	3.8	1.06	20	35	<5	1.08	1	11	141	1969	3.65	<10	1.11	976	104	0.02	5	1200	14	<5	<20	71	<0.01	<10	21	<10	5	61
16	X09567	5.1	0.86	25	40	<5	1.52	2	9	135	2186	3.94	<10	0.90	1396	61	0.02	4	1200	28	<5	<20	85	<0.01	<10	18	<10	4	48
17	X09568	3.4	0.81	35	40	<5	1.70	2	10	145	1510	3.85	<10	0.75	1182	63	0.02	4	1260	14	<5	<20	90	<0.01	<10	18	<10	5	44
18	X09569	4.3	1.07	30	40	<5	1.50	2	11	154	1923	3.82	<10	1.11	1332	48	0.02	5	1220	42	<5	<20	81	<0.01	<10	22	<10	4	82
19	X09570	2.0	1.67	25	50	<5	1.34	1	13	139	1126	4.68	<10	1.67	1396	68	0.02	5	1480	24	<5	<20	79	<0.01	<10	31	<10	4	145
20	X09571	2.9	1.05	20	40	<5	2.24	2	11	125	1519	3.90	<10	1.08	1246	34	0.02	4	1270	56	<5	<20	145	<0.01	<10	20	<10	5	95
21	X09572	<0.2	1.00	10	245	<5	0.59	<1	6	145	4	2.17	<10	0.56	537	2	0.10	7	910	<2	<5	<20	84	0.14	<10	39	<10	5	41
22	X09573	4.8	0.73	20	40	<5	3.13	2	10	136	1966	3.64	<10	0.99	2394	61	0.02	5	1210	18	<5	<20	212	<0.01	<10	13	<10	6	50
23	X09574	4.9	1.04	20	35	<5	0.95	2	11	151	2675	3.88	<10	1.05	930	231	0.02	5	1360	14	<5	<20	63	<0.01	<10	21	<10	5	108
24	X09575	2.6	1.04	20	40	<5	1.20	2	12	111	1307	4.20	<10	1.09	1323	60	0.02	4	1420	24	<5	<20	68	<0.01	<10	22	<10	5	111
25	X09576	8.8	0.64	20	35	15	0.88	5	9	140	1807	5.07	<10	0.59	1140	34	0.02	3	1420	476	<5	<20	53	<0.01	<10	16	<10	5	194

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007-5636 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09577	5.7	0.44	20	30	<5	0.52	2	11	185	2680	3.95	<10	0.27	656	64	0.02	4	1110	54	<5	<20	34	<0.01	<10	10	<10	4	54
27	X09578	4.8	0.39	25	30	<5	0.89	2	11	131	1374	4.40	<10	0.16	751	61	0.02	3	1220	144	<5	<20	57	<0.01	<10	10	<10	4	41
28	X09579	3.1	0.95	15	45	<5	1.12	1	10	105	1599	3.26	<10	1.02	1213	57	0.02	4	1310	12	<5	<20	83	<0.01	<10	20	<10	5	75
29	X09580	1.4	1.08	15	40	<5	0.86	1	12	127	1409	3.79	<10	0.92	598	70	0.04	4	1300	8	<5	<20	73	<0.01	<10	35	<10	5	59
30	X09581	2.4	0.92	15	40	<5	0.73	1	11	121	2102	3.41	<10	0.77	572	81	0.03	4	1220	14	<5	<20	57	<0.01	<10	22	<10	5	54
31	X09582	1.5	0.94	15	45	<5	0.70	1	11	156	1371	3.28	<10	0.74	629	56	0.03	5	1170	10	<5	<20	83	<0.01	<10	31	<10	4	63
32	X09583	2.2	0.90	25	30	<5	0.77	2	10	127	1861	4.13	<10	0.79	693	64	0.03	3	1210	16	<5	<20	62	<0.01	<10	24	<10	4	67
33	X09584	0.2	1.02	110	105	10	0.29	5	66	274	412	>10	10	0.14	434	104	0.07	458	210	124	5	<20	15	<0.01	<10	19	<10	6	394
34	X09585	1.1	1.10	15	55	<5	0.88	1	10	131	1240	3.42	<10	1.01	819	90	0.03	4	1220	10	<5	<20	73	<0.01	<10	35	<10	5	77
35	X09586	<0.2	0.90	20	30	<5	0.60	2	12	154	1642	3.75	<10	0.68	641	66	0.03	4	1140	22	<5	<20	42	<0.01	<10	23	<10	4	67
QC DATA:																													
Repeat:																													
1	X09552	3.8	0.83	20	35	<5	0.61	1	10	162	1831	3.92	<10	0.82	695	70	0.02	5	1190	22	<5	<20	42	<0.01	<10	19	<10	4	50
10	X09561	3.2	1.35	15	40	<5	1.46	2	11	137	2409	4.48	<10	1.24	1041	63	0.02	4	1220	12	<5	<20	102	<0.01	<10	24	<10	5	73
19	X09570	2.1	1.62	25	50	<5	1.34	2	14	145	1132	4.83	<10	1.63	1455	73	0.02	5	1520	26	<5	<20	83	<0.01	<10	32	<10	4	152
Resplit:																													
1	X09552	3.8	0.97	20	35	<5	0.64	2	12	162	1778	4.05	<10	0.84	705	80	0.02	6	1250	24	<5	<20	45	<0.01	<10	21	<10	5	51
Standard:																													
Pb113A		11.2	0.30	40	70	<5	1.84	42	2	1	2245	1.05	<10	0.11	1516	61	0.02	1	100	5512	5	<20	106	0.01	<10	7	<10	1	6924

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/n5636
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5637

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

14-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07148
Submitted by: Peter Erwick

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09587	0.68	0.020
2	X09588	0.54	0.016
3	X09589	0.70	0.020
4	X09590	0.68	0.020
5	X09591	0.83	0.024
6	X09592	0.65	0.019
7	X09593	0.55	0.016
8	X09594	0.37	0.011
9	X09595	0.33	0.010
10	X09596	0.68	0.020
11	X09597	<0.03	<0.001
12	X09598	0.56	0.016
13	X09599	0.69	0.020
14	X09600	0.58	0.017
15	X09601	0.11	0.003
16	X09602	0.36	0.010
17	X09603	0.36	0.010
18	X09604	0.52	0.015
19	X09605	0.37	0.011
20	X09606	0.44	0.013
21	X09607	0.44	0.013
22	X09608	0.39	0.011
23	X09609	0.52	0.015
24	X09610	0.49	0.014
25	X09611	0.53	0.015

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5637 14-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X09612	0.53	0.015
27	X09613	0.52	0.015
28	X09614	0.32	0.009
29	X09615	0.49	0.014
30	X09616	0.45	0.013
31	X09617	0.31	0.009
32	X09618	0.55	0.016
33	X09619	0.42	0.012
34	X09620	0.99	0.029
35	X09621	0.42	0.012

QC DATA:

Repeat:

1	X09587	0.70	0.020
5	X09591	0.95	0.028
10	X09596	0.70	0.020
19	X09605	0.34	0.010

Resplits:

1	X09587	0.62	0.018

Standard:

OXi54		1.83	0.053

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

15-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5637

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07148
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09587	2.6	1.13	15	40	<5	1.15	1	10	105	1212	3.44	<10	1.08	1009	470	0.03	4	1260	16	<5	<20	68	<0.01	<10	29	<10	5	85
2	X09588	1.2	1.24	20	45	<5	0.83	2	11	107	1294	3.59	<10	1.00	767	56	0.03	4	1360	50	<5	<20	61	<0.01	<10	34	<10	4	96
3	X09589	1.3	1.14	15	55	<5	0.55	2	11	124	1729	3.22	<10	0.87	530	72	0.03	4	1220	8	<5	<20	43	<0.01	<10	33	<10	4	71
4	X09590	1.9	1.05	15	35	<5	0.75	2	10	96	1457	3.71	<10	0.87	549	79	0.04	4	1280	10	<5	<20	57	<0.01	<10	36	<10	6	55
5	X09591	2.1	1.01	15	40	<5	0.55	1	11	107	2362	2.96	<10	0.74	388	91	0.03	4	1210	10	<5	<20	45	<0.01	<10	28	<10	5	47
6	X09592	1.4	1.35	15	60	<5	1.58	2	12	103	1524	3.56	<10	0.99	781	61	0.03	10	1350	8	<5	<20	125	<0.01	<10	32	<10	4	67
7	X09593	2.1	1.14	20	45	<5	1.38	2	11	106	1132	3.32	<10	0.71	744	71	0.02	4	1410	10	<5	<20	98	<0.01	<10	25	<10	4	64
8	X09594	4.7	0.59	30	30	<5	2.06	2	11	122	1603	3.71	<10	0.33	1068	62	0.02	4	1510	90	<5	<20	139	<0.01	<10	12	<10	5	34
9	X09595	4.3	0.67	20	35	<5	2.59	2	10	111	1380	3.26	<10	0.39	1072	79	0.02	11	1190	116	<5	<20	191	<0.01	<10	15	<10	5	35
10	X09596	6.6	0.31	40	35	<5	2.62	6	9	117	1878	4.90	<10	0.20	1322	254	0.02	3	1230	102	5	<20	180	<0.01	<10	7	<10	5	125
11	X09597	<0.2	1.10	10	270	<5	0.62	<1	7	103	4	2.33	<10	0.54	616	4	0.10	7	950	8	<5	<20	79	0.16	<10	44	<10	5	49
12	X09598	4.2	0.69	20	40	<5	2.88	2	12	111	1369	3.74	<10	0.49	1226	61	0.02	4	1410	20	<5	<20	142	<0.01	<10	15	<10	5	51
13	X09599	4.3	0.65	20	40	<5	4.36	2	12	118	1424	3.26	<10	0.45	1657	92	0.02	4	1300	12	<5	<20	231	<0.01	<10	15	<10	6	41
14	X09600	2.6	1.08	15	60	<5	3.41	2	15	116	1405	2.98	<10	0.70	1063	65	0.02	5	1350	8	<5	<20	218	<0.01	<10	21	<10	5	58
15	X09601	0.6	3.38	40	145	<5	5.10	2	34	159	328	5.60	<10	3.41	1619	8	0.02	89	830	2	<5	<20	253	<0.01	<10	60	<10	6	93
16	X09602	3.3	0.95	35	40	<5	4.12	2	17	109	852	4.75	<10	0.68	1391	69	0.02	14	1340	40	<5	<20	278	<0.01	<10	19	<10	5	47
17	X09603	2.2	1.53	25	65	<5	6.67	2	19	109	774	4.06	<10	1.27	2160	32	0.02	32	1120	12	<5	<20	342	<0.01	<10	26	<10	6	107
18	X09604	2.1	1.23	20	65	<5	3.57	2	11	92	1314	3.41	<10	0.81	1088	54	0.02	4	1390	8	<5	<20	268	<0.01	<10	31	<10	5	68
19	X09605	1.5	1.26	15	90	<5	3.08	2	10	93	928	3.55	<10	0.89	1025	46	0.02	4	1510	8	<5	<20	233	<0.01	<10	30	<10	5	82
20	X09606	4.8	0.72	30	40	<5	1.89	2	13	110	1719	3.97	<10	0.62	1084	181	0.02	4	1640	46	<5	<20	99	<0.01	<10	19	<10	6	70
21	X09607	7.0	0.89	30	45	<5	2.95	2	12	126	2463	3.76	<10	0.93	1625	63	0.02	4	1390	106	5	<20	160	<0.01	<10	20	<10	6	86
22	X09608	3.4	0.80	25	45	<5	2.97	2	12	127	1724	3.55	<10	0.94	1764	62	0.02	4	1280	32	<5	<20	134	<0.01	<10	19	<10	6	61
23	X09609	4.5	0.88	30	45	<5	3.55	2	14	114	1999	3.83	<10	0.81	1748	74	0.02	4	1470	26	<5	<20	160	<0.01	<10	20	<10	6	81
24	X09610	8.6	0.95	35	45	<5	2.38	2	14	130	2133	4.24	<10	0.86	1366	82	0.02	4	1390	40	5	<20	134	<0.01	<10	26	<10	7	87
25	X09611	3.5	1.01	20	65	<5	4.17	2	12	90	1082	2.97	<10	0.63	1625	43	0.02	4	1670	10	<5	<20	279	<0.01	<10	21	<10	5	106

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09612	4.7	1.02	15	60	<5	3.83	2	11	87	1588	2.83	<10	0.64	1359	49	0.02	4	1640	18	<5	<20	242	<0.01	<10	22	<10	6	91
27	X09613	2.6	1.02	15	50	<5	4.34	2	13	92	1340	3.17	<10	0.65	1415	125	0.02	4	1560	18	<5	<20	291	<0.01	<10	26	<10	6	82
28	X09614	1.4	1.26	15	75	<5	3.17	2	12	72	1056	3.52	<10	0.82	1288	45	0.02	3	1560	14	<5	<20	262	<0.01	<10	29	<10	5	93
29	X09615	3.7	0.91	30	45	<5	4.93	2	13	120	1282	4.01	<10	0.67	1807	55	0.02	4	1540	20	<5	<20	259	<0.01	<10	19	<10	7	75
30	X09616	3.4	0.90	25	40	<5	5.92	2	13	68	1160	3.97	<10	0.66	2253	52	0.02	3	1560	24	<5	<20	298	<0.01	<10	19	<10	8	73
31	X09617	3.2	0.98	15	55	<5	3.06	2	14	96	1217	3.54	<10	0.60	1260	69	0.02	4	1630	10	<5	<20	243	<0.01	<10	24	<10	6	80
32	X09618	2.8	1.22	15	45	<5	3.10	2	23	104	2162	4.53	<10	0.83	1029	240	0.03	5	1500	30	<5	<20	223	<0.01	<10	42	<10	7	93
33	X09619	2.1	1.11	15	60	<5	3.17	2	12	157	1246	3.27	<10	0.70	1119	78	0.03	5	1360	14	<5	<20	243	<0.01	<10	33	<10	5	77
34	X09620	3.7	1.22	70	100	10	0.91	5	17	68	3317	4.05	20	0.43	330	228	0.03	18	400	126	40	<20	42	0.04	<10	41	<10	8	171
35	X09621	4.1	1.16	25	50	<5	5.76	3	13	89	1252	3.85	<10	1.18	2844	62	0.02	3	1500	28	5	<20	375	<0.01	<10	27	<10	6	80
QC DATA:																													
Repeat:																													
1	X09587	2.6	1.19	15	40	<5	1.09	2	11	108	1264	3.56	<10	1.06	1076	495	0.03	4	1300	16	<5	<20	74	<0.01	<10	32	<10	5	89
10	X09596	6.5	0.33	45	35	<5	2.69	6	10	114	1832	5.22	<10	0.21	1379	254	0.02	3	1290	112	10	<20	179	<0.01	<10	7	<10	5	126
19	X09605	1.5	1.36	15	95	<5	3.24	2	11	103	967	3.70	<10	0.90	1090	52	0.02	4	1590	8	<5	<20	241	<0.01	<10	32	<10	6	86
Resplit:																													
1	X09587	2.4	1.21	20	45	<5	1.19	2	14	105	1287	3.90	<10	1.11	1098	485	0.02	4	1260	20	<5	<20	67	<0.01	<10	33	<10	5	85
Standard:																													
Pb113A		10.8	0.30	65	75	<5	2.31	58	2	2	2254	1.21	<10	0.10	1515	67	0.01	1	100	5574	5	<20	105	0.01	<10	8	<10	1	7149

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/n5636
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5638

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

14-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07149
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05083	0.71	0.021
2	X05084	1.18	0.034
3	X05085	0.87	0.025
4	X05086	1.36	0.040
5	X05087	1.27	0.037
6	X05088	0.60	0.017
7	X05089	0.56	0.016
8	X05090	0.42	0.012
9	X05091	0.38	0.011
10	X05092	0.67	0.020
11	X05093	0.64	0.019
12	X05094	0.74	0.022
13	X05095	0.60	0.017
14	X05096	<0.03	<0.001
15	X05097	0.45	0.013
16	X05098	0.74	0.022
17	X05099	0.64	0.019
18	X05100	1.89	0.055
19	X05151	0.42	0.012
20	X05152	0.51	0.015
21	X05153	0.55	0.016
22	X05154	0.60	0.017
23	X05155	0.55	0.016
24	X05156	0.56	0.016
25	X05157	1.23	0.036

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AK7-5638 14-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X05158	1.09	0.032
27	X05159	0.75	0.022
28	X05160	0.75	0.022
29	X05161	1.01	0.029
30	X05162	0.78	0.023
31	X05163	0.55	0.016
32	X05164	0.83	0.024
33	X05165	0.69	0.020
34	X05166	0.72	0.021
35	X05167	0.59	0.017

QC DATA:

Repeat:

1	X05083	0.67	0.020
4	X05086	1.16	0.034
10	X05092	0.66	0.019
18	X05100	1.93	0.056
19	X05151	0.50	0.015

Resplits:

1	X05083	0.74	0.022

Standard:

OXI54		1.83	0.053

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

15-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5638

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07149
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05083	3.0	0.32	10	30	<5	2.87	3	13	169	3380	3.49	<10	0.08	432	9	0.02	2	940	46	<5	<20	189	<0.01	<10	8	<10	3	72
2	X05084	3.6	0.43	10	35	<5	2.36	3	12	153	3866	3.68	<10	0.19	315	5	0.02	2	890	50	<5	<20	277	<0.01	<10	13	<10	3	59
3	X05085	2.2	0.59	10	40	<5	2.81	2	7	137	2429	3.10	<10	0.31	427	10	0.02	2	1060	20	<5	<20	286	<0.01	<10	18	<10	3	67
4	X05086	3.4	0.40	10	35	<5	3.76	2	9	198	3405	3.27	<10	0.17	514	9	0.01	3	670	20	<5	<20	276	<0.01	<10	13	<10	2	39
5	X05087	6.2	0.50	15	35	<5	2.39	4	17	146	4674	5.76	<10	0.39	1134	8	0.02	1	1040	60	<5	<20	87	<0.01	<10	16	<10	3	93
6	X05088	3.0	0.64	25	35	<5	2.52	2	7	151	1684	4.08	<10	0.49	1351	9	0.01	2	1190	28	5	<20	92	<0.01	<10	12	<10	4	86
7	X05089	4.9	0.31	30	30	<5	2.04	6	9	182	1913	4.33	<10	0.10	1138	67	0.01	2	1040	86	15	<20	113	<0.01	<10	7	<10	3	220
8	X05090	4.9	0.27	70	30	<5	1.83	4	8	190	3990	4.13	<10	0.12	976	6	0.01	2	820	48	85	<20	62	<0.01	<10	6	<10	2	107
9	X05091	3.4	0.41	25	40	<5	3.06	3	7	193	1885	2.82	<10	0.15	951	13	0.02	3	1140	30	5	<20	106	<0.01	<10	8	<10	3	109
10	X05092	5.3	0.67	15	40	<5	4.01	3	8	144	2014	4.44	<10	0.38	951	5	0.02	2	1100	40	<5	<20	298	<0.01	<10	23	<10	4	104
11	X05093	5.1	0.68	20	40	<5	3.76	2	9	146	2171	3.63	<10	0.31	1108	11	0.02	2	1100	22	<5	<20	203	<0.01	<10	17	<10	4	74
12	X05094	5.2	0.51	45	35	<5	2.57	2	7	159	1403	3.63	<10	0.19	1141	7	0.01	3	1090	38	5	<20	51	<0.01	<10	9	<10	3	70
13	X05095	8.5	0.51	35	40	<5	1.80	4	9	180	2721	4.26	<10	0.16	839	10	0.01	2	1030	68	5	<20	34	<0.01	<10	10	<10	3	122
14	X05096	<0.2	1.20	10	295	<5	0.70	1	9	101	4	2.17	<10	0.54	549	<1	0.09	8	950	8	<5	<20	91	0.19	<10	46	<10	6	53
15	X05097	10.9	0.65	20	45	15	1.28	8	11	104	2883	4.23	<10	0.21	794	6	0.02	2	1340	110	<5	<20	21	<0.01	<10	11	<10	3	324
16	X05098	8.5	0.80	25	35	<5	3.14	3	10	116	3106	3.84	<10	0.38	1615	10	0.02	2	1310	54	<5	<20	112	<0.01	<10	11	<10	5	152
17	X05099	2.1	0.95	15	70	<5	2.06	3	8	114	1959	3.51	<10	0.55	657	5	0.02	2	1160	34	<5	<20	142	<0.01	<10	20	<10	3	183
18	X05100	3.9	1.29	45	45	<5	1.10	4	24	61	8738	4.15	20	0.55	284	744	0.04	77	690	60	20	<20	82	0.06	<10	42	<10	8	100
19	X05151	5.4	0.45	20	35	<5	3.01	7	15	175	4673	4.72	<10	0.19	769	9	0.02	2	830	132	<5	<20	206	<0.01	<10	12	<10	2	301
20	X05152	3.2	0.56	15	35	<5	3.07	2	8	195	2894	3.79	<10	0.27	664	8	0.02	3	850	26	<5	<20	241	<0.01	<10	15	<10	2	91
21	X05153	3.1	0.54	20	45	<5	2.88	3	8	138	2966	3.40	<10	0.25	902	10	0.02	2	1260	42	<5	<20	146	<0.01	<10	12	<10	3	122
22	X05154	2.7	0.50	15	40	<5	4.14	3	13	151	2336	3.91	<10	0.21	1135	10	0.01	2	1080	54	<5	<20	192	<0.01	<10	12	<10	3	96
23	X05155	2.6	0.68	15	50	<5	1.86	4	10	187	2079	3.92	<10	0.36	717	13	0.02	3	1110	36	<5	<20	106	<0.01	<10	22	<10	3	139
24	X05156	4.2	1.07	20	60	10	1.55	4	9	214	3093	6.29	<10	0.68	915	5	0.02	2	700	36	<5	<20	41	<0.01	<10	34	<10	2	196
25	X05157	5.6	0.72	15	40	10	1.43	4	12	151	4630	5.45	<10	0.34	654	8	0.02	<1	1150	54	<5	<20	69	<0.01	<10	16	<10	2	132

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05158	3.7	0.74	15	45	<5	1.69	3	10	165	3431	4.30	<10	0.39	667	7	0.02	2	1040	34	<5	<20	141	<0.01	<10	18	<10	3	131
27	X05159	2.2	0.88	20	50	<5	1.44	3	9	164	1777	4.12	<10	0.48	683	11	0.02	2	1150	24	<5	<20	111	<0.01	<10	19	<10	3	154
28	X05160	2.2	0.78	15	50	<5	0.55	3	10	176	1803	4.84	<10	0.46	635	7	0.02	3	980	42	<5	<20	43	<0.01	<10	21	<10	3	195
29	X05161	2.7	0.86	15	75	<5	0.90	2	8	131	1961	4.14	<10	0.48	639	10	0.02	1	1040	40	<5	<20	79	<0.01	<10	22	<10	3	146
30	X05162	5.0	1.11	15	65	<5	1.43	4	8	170	2710	4.30	<10	0.59	895	9	0.02	3	1100	118	<5	<20	55	<0.01	<10	19	<10	3	268
31	X05163	5.7	0.61	20	40	<5	1.11	9	9	200	1874	4.11	<10	0.31	844	12	0.02	3	1020	92	<5	<20	26	<0.01	<10	9	<10	3	395
32	X05164	4.7	0.93	25	50	<5	1.17	4	10	153	2879	4.37	<10	0.48	885	8	0.01	2	1120	60	<5	<20	26	<0.01	<10	12	<10	3	170
33	X05165	6.4	0.61	45	35	<5	2.27	4	12	162	2826	5.01	<10	0.26	944	11	0.01	2	1120	74	10	<20	98	<0.01	10	10	<10	3	162
34	X05166	5.2	0.69	35	35	<5	2.17	4	11	207	2600	4.60	<10	0.30	944	8	0.01	3	1030	68	10	<20	85	<0.01	<10	11	<10	3	150
35	X05167	2.3	0.92	15	55	<5	1.44	2	9	198	1897	3.72	<10	0.50	746	16	0.01	3	1140	26	<5	<20	57	<0.01	<10	16	<10	3	103
QC DATA:																													
Repeat:																													
1	X05083	3.0	0.36	5	35	<5	3.04	3	13	179	3416	3.53	<10	0.08	445	8	0.01	3	970	42	<5	<20	193	<0.01	<10	8	<10	3	71
10	X05092	5.2	0.70	15	40	<5	4.13	3	8	145	2005	4.37	<10	0.38	945	7	0.02	2	1080	40	<5	<20	304	<0.01	<10	24	<10	4	103
19	X05151	5.6	0.47	20	40	<5	3.02	7	15	177	4574	4.72	<10	0.19	760	9	0.02	2	810	132	<5	<20	207	<0.01	<10	12	<10	2	299
Resplit:																													
1	X05083	2.8	0.37	5	30	<5	2.84	3	12	175	3366	3.61	<10	0.07	433	10	0.01	2	1050	44	<5	<20	182	<0.01	<10	9	<10	3	68
Standard:																													
Pb113A		11.2	0.33	65	85	<5	1.64	59	2	2	2412	1.24	<10	0.10	1556	66	0.01	1	90	5506	5	<20	89	0.01	<10	8	<10	1	7135

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

JJ/nl
df/n5636
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5642

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

20-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07150
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09622	0.42	0.012
2	X09623	0.51	0.015
3	X09624	0.90	0.026
4	X09625	0.62	0.018
5	X09626	0.37	0.011
6	X09627	0.43	0.013
7	X09628	0.51	0.015
8	X09629	0.55	0.016
9	X09630	0.67	0.020
10	X09631	0.60	0.017
11	X09632	0.70	0.020
12	X09633	0.63	0.018
13	X09634	1.01	0.029
14	X09635	0.74	0.022
15	X09636	0.98	0.029
16	X09637	1.70	0.050
17	X09638	0.86	0.025
18	X09639	1.23	0.036
19	X09640	0.74	0.022
20	X09641	0.95	0.028
21	X09642	1.11	0.032
22	X09643	<0.03	<0.001
23	X09644	0.79	0.023
24	X09645	0.80	0.023
25	X09646	0.68	0.020

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5642 20-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X09647	0.48	0.014
27	X09648	1.83	0.053
28	X09649	0.45	0.013
29	X09650	0.65	0.019
30	X09651	1.05	0.031
31	X09652	0.67	0.020
32	X09653	0.73	0.021
33	X09654	0.95	0.028
34	X09655	2.50	0.073
35	X09656	0.88	0.026
QC DATA:			
Repeat:			
1	X09622	0.40	0.012
3	X09624	0.89	0.026
10	X09631	0.52	0.015
13	X09634	1.03	0.030
19	X09640	0.80	0.023
21	X09642	1.10	0.032
30	X09651	1.13	0.033
34	X09655	2.39	0.070
Resplits:			
1	X09622	0.57	0.017
Standard:			
OXi54		1.86	0.054

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

16-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5642

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07150
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09622	4.7	0.97	15	50	<5	4.12	2	9	55	1313	2.75	<10	1.19	1489	30	0.02	3	1380	22	<5	<20	221	<0.01	<10	21	<10	6	46
2	X09623	2.0	1.00	10	65	<5	2.99	1	7	65	1676	2.56	<10	0.91	812	63	0.02	3	1280	18	<5	<20	159	<0.01	<10	23	<10	6	49
3	X09624	7.9	1.25	20	50	<5	2.57	2	8	87	3154	3.03	<10	1.45	1189	116	0.02	3	1090	28	5	<20	128	<0.01	<10	22	<10	6	51
4	X09625	5.6	1.08	25	40	<5	2.19	2	10	69	1542	3.18	<10	1.18	996	80	0.02	3	1450	16	<5	<20	98	<0.01	<10	23	<10	6	44
5	X09626	3.5	1.06	15	50	<5	3.12	2	11	63	1228	2.91	<10	1.15	1330	60	0.03	3	1260	12	<5	<20	163	<0.01	<10	18	<10	6	47
6	X09627	2.5	1.15	15	60	<5	3.15	1	12	59	947	2.95	<10	1.08	1076	27	0.02	3	1370	8	<5	<20	147	<0.01	<10	22	<10	6	51
7	X09628	4.6	1.06	15	45	<5	3.20	1	8	69	1118	2.88	<10	1.07	1355	106	0.02	3	1290	10	<5	<20	143	<0.01	<10	20	<10	7	56
8	X09629	5.1	0.73	20	40	<5	3.62	2	9	85	1415	2.82	<10	0.64	1160	46	0.01	3	1230	20	<5	<20	140	<0.01	<10	16	<10	7	52
9	X09630	1.7	1.13	20	35	<5	1.71	6	8	68	1595	3.78	<10	1.33	1189	13	0.01	2	1100	52	<5	<20	25	<0.01	<10	16	<10	6	269
10	X09631	0.6	1.94	15	70	<5	1.00	2	7	62	1186	3.90	<10	1.75	689	13	0.01	2	1160	6	<5	<20	26	<0.01	<10	20	<10	5	160
11	X09632	1.1	1.26	10	45	<5	1.72	2	7	72	1385	3.54	<10	1.32	1005	11	0.01	2	1060	12	<5	<20	29	<0.01	<10	14	<10	5	100
12	X09633	1.0	1.65	20	45	<5	0.86	2	10	74	1211	4.70	<10	1.36	841	16	0.01	2	1240	10	<5	<20	19	<0.01	<10	20	<10	6	133
13	X09634	1.5	1.09	20	40	<5	1.43	2	8	91	1886	4.05	<10	1.07	823	11	0.02	2	1080	34	<5	<20	36	<0.01	<10	13	<10	4	91
14	X09635	1.2	0.86	60	40	<5	1.60	2	7	68	1667	3.39	<10	1.03	870	9	0.01	2	1180	22	5	<20	22	<0.01	<10	12	<10	5	92
15	X09636	1.3	0.89	35	40	<5	1.59	2	7	85	1477	3.40	<10	1.01	957	18	0.01	2	1060	20	<5	<20	23	<0.01	<10	12	<10	5	86
16	X09637	2.1	1.01	50	35	<5	0.53	2	9	89	2233	4.49	<10	0.78	342	17	0.01	1	1140	54	<5	<20	14	<0.01	<10	14	<10	4	134
17	X09638	1.2	1.30	20	50	<5	1.23	2	7	66	1673	3.86	<10	1.16	686	12	0.01	1	1090	62	<5	<20	25	<0.01	<10	16	<10	4	141
18	X09639	2.0	1.06	15	40	<5	2.05	2	10	77	2835	3.85	<10	1.14	790	11	0.01	1	1000	40	<5	<20	52	<0.01	<10	12	<10	5	89
19	X09640	1.3	1.43	20	50	<5	1.82	2	9	64	1522	3.88	<10	1.41	753	21	0.02	2	1070	14	<5	<20	59	<0.01	<10	19	<10	6	82
20	X09641	1.7	1.20	15	45	<5	2.07	2	8	84	2109	3.98	<10	1.42	903	6	0.01	1	920	40	<5	<20	118	<0.01	<10	15	<10	5	73
21	X09642	1.3	1.66	15	60	<5	2.52	2	7	90	1935	4.11	<10	1.46	800	8	0.02	2	960	12	<5	<20	205	<0.01	<10	25	<10	5	90
22	X09643	<0.2	1.09	5	240	<5	0.70	<1	6	110	4	2.11	<10	0.61	514	<1	0.10	7	950	<2	<5	<20	84	0.13	<10	37	<10	4	38
23	X09644	1.0	1.48	15	55	<5	2.61	2	7	79	1486	3.80	<10	1.68	1072	8	0.02	2	1070	14	<5	<20	114	<0.01	<10	15	<10	6	102
24	X09645	0.9	1.59	15	75	<5	2.24	2	7	57	1415	3.59	<10	1.57	1047	10	0.02	2	1060	22	<5	<20	109	<0.01	<10	17	<10	6	108
25	X09646	0.9	1.65	15	100	<5	2.61	2	7	68	1169	3.67	<10	1.60	1240	8	0.02	2	1060	8	<5	<20	120	<0.01	<10	16	<10	6	112

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09647	1.4	1.10	20	50	<5	3.18	2	7	66	1198	3.71	<10	1.56	1658	10	0.01	2	1060	24	<5	<20	57	<0.01	<10	13	<10	6	134
27	X09648	4.0	1.14	35	45	<5	1.17	3	17	54	8563	3.99	20	0.63	187	553	0.04	55	590	44	20	<20	56	0.04	<10	36	<10	8	66
28	X09649	1.2	1.37	15	55	<5	2.70	2	7	62	822	3.77	<10	1.48	1405	11	0.01	2	1080	10	<5	<20	51	<0.01	<10	12	<10	5	109
29	X09650	2.2	1.10	25	50	<5	2.86	2	7	71	1527	3.45	<10	1.23	1310	11	0.01	2	1010	10	<5	<20	58	<0.01	<10	10	<10	6	84
30	X09651	3.0	0.60	40	40	<5	2.33	3	7	73	2132	3.62	<10	1.03	1445	7	0.01	1	1130	18	5	<20	35	<0.01	<10	6	<10	6	97
31	X09652	4.8	0.27	55	30	<5	1.01	2	8	105	3033	4.45	<10	0.31	540	5	0.02	<1	830	62	20	<20	19	<0.01	<10	3	<10	2	27
32	X09653	2.7	0.43	45	40	<5	1.91	2	6	73	1502	3.56	<10	0.80	1040	7	0.01	1	1070	30	15	<20	35	<0.01	<10	6	<10	4	55
33	X09654	2.3	0.53	45	40	<5	2.03	2	6	60	1498	3.30	<10	0.87	1124	5	0.02	1	1140	18	5	<20	29	<0.01	<10	6	<10	5	71
34	X09655	3.3	0.76	65	35	<5	1.16	3	6	67	1353	3.32	<10	0.79	741	7	0.02	1	1030	20	10	<20	22	<0.01	<10	6	<10	4	145
35	X09656	3.0	0.96	50	45	<5	0.80	2	6	87	1849	2.92	<10	0.76	451	7	0.02	3	1110	8	15	<20	13	<0.01	<10	7	<10	5	134
QC DATA:																													
Repeat:																													
1	X09622	4.5	1.02	15	60	<5	4.32	2	9	58	1304	2.80	<10	1.22	1515	24	0.02	3	1390	24	<5	<20	226	<0.01	<10	20	<10	6	48
10	X09631	0.9	1.97	15	75	<5	1.01	2	7	64	1190	3.96	<10	1.77	693	12	0.01	2	1160	4	<5	<20	28	<0.01	<10	21	<10	5	162
19	X09640	1.4	1.46	20	50	<5	1.85	2	9	66	1514	3.84	<10	1.38	758	21	0.02	2	1070	14	<5	<20	60	<0.01	<10	17	<10	6	83
Resplit:																													
1	X09622	4.5	1.05	15	50	<5	4.12	2	8	63	1383	2.75	<10	1.17	1467	26	0.03	3	1340	20	5	<20	218	<0.01	<10	20	<10	6	39
Standard:																													
Pb113A		11.1	0.29	40	55	<5	1.69	38	2	<1	2158	0.90	<10	0.10	1464	65	0.02	2	90	5472	10	<20	82	<0.01	<10	5	<10	1	6935

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/n5642
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5643

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

20-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07151
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	X09657	1.50	0.044		
2	X09658	2.70	0.079		
3	X09659	1.87	0.055		
4	X09660	1.99	0.058		
5	X09661	2.40	0.070		
6	X09662	1.43	0.042		
7	X09663	1.17	0.034		
8	X09664	0.91	0.027		
9	X09665	<0.03	<0.001		
10	X09666	1.51	0.044	42.2	1.23
11	X09667	1.10	0.032		
12	X09668	1.07	0.031		
13	X09669	0.84	0.024		
14	X09670	0.91	0.027		
15	X09671	0.49	0.014	167	4.87
16	X09672	0.50	0.015	40.9	1.19
17	X09673	1.32	0.038		
18	X09674	0.61	0.018		
19	X09675	0.67	0.020		
20	X09676	1.19	0.035		
21	X09677	1.17	0.034		
22	X09678	1.28	0.037		
23	X09679	0.71	0.021		
24	X09680	0.37	0.011		
25	X09681	0.58	0.017		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5643 20-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
26	X09682	0.68	0.020		
27	X09683	0.30	0.009		
28	X09684	0.84	0.024		
29	X09685	1.08	0.031		
30	X09686	1.27	0.037		
31	X09687	0.98	0.029		
32	X09688	1.24	0.036		
33	X09689	1.64	0.048		
34	X09690	0.57	0.017		
35	X09691	0.64	0.019		
QC DATA:					
Repeat:					
1	X09657	1.56	0.045		
2	X09658	2.90	0.085		
3	X09659	1.87	0.055		
5	X09661	2.35	0.069		
6	X09662	1.46	0.043		
10	X09666	1.61	0.047	43.2	1.26
19	X09675	0.67	0.020		
29	X09685	1.07	0.031		
30	X09686	1.33	0.039		
31	X09687	1.02	0.030		
33	X09689	1.67	0.049		
Resplits:					
1	X09657	1.55	0.045		
Standard:					
OXi54		1.88	0.055		
Pb113				22.6	0.66

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
XLS/07

16-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5643

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07151
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09657	4.9	0.55	75	35	<5	0.99	3	7	84	1734	3.85	<10	0.50	530	9	0.02	2	1000	38	15	<20	17	<0.01	<10	6	<10	4	98
2	X09658	8.8	0.77	160	50	<5	3.52	13	31	225	4783	3.70	<10	0.26	2374	17	0.08	<1	2230	232	40	<20	49	0.01	<10	30	<10	3	521
3	X09659	9.8	0.29	170	35	<5	0.69	4	7	126	3030	3.61	<10	0.25	452	5	0.01	2	840	90	60	<20	18	<0.01	<10	4	<10	3	144
4	X09660	8.8	0.47	165	40	<5	1.24	4	8	102	2451	3.81	<10	0.63	1030	5	0.01	2	870	82	50	<20	30	<0.01	<10	5	<10	4	163
5	X09661	3.4	0.68	145	40	<5	0.71	5	8	78	1359	4.66	<10	0.57	604	7	0.01	2	1160	18	10	<20	16	<0.01	<10	8	<10	4	192
6	X09662	4.2	0.85	75	45	<5	0.89	3	7	83	1985	3.59	<10	0.77	873	6	0.01	2	1030	28	5	<20	20	<0.01	<10	7	<10	5	147
7	X09663	3.8	0.90	85	40	<5	0.91	3	8	87	1896	4.02	<10	0.83	984	8	0.01	2	1130	24	10	<20	20	<0.01	<10	7	<10	5	148
8	X09664	3.2	0.89	100	45	<5	0.98	3	9	75	1331	4.35	<10	0.87	1176	10	0.01	2	1100	18	10	<20	21	<0.01	<10	9	<10	4	131
9	X09665	<0.2	1.00	10	235	<5	0.57	1	6	98	4	2.06	<10	0.54	516	<1	0.09	6	860	10	<5	<20	84	0.13	<10	39	<10	4	47
10	X09666	>30	0.40	160	35	<5	0.44	6	6	110	2199	3.85	<10	0.20	349	9	0.01	2	1000	216	90	<20	16	<0.01	<10	7	<10	4	274
11	X09667	4.4	0.56	100	40	<5	0.89	9	7	89	1231	4.55	<10	0.52	901	7	0.01	2	1070	292	10	<20	19	<0.01	<10	8	<10	4	540
12	X09668	3.0	1.09	90	45	<5	0.66	4	8	80	1618	4.58	<10	0.92	718	7	0.01	1	1100	24	5	<20	18	<0.01	<10	10	<10	5	232
13	X09669	4.9	0.67	65	40	<5	1.07	5	8	104	2186	4.27	<10	0.60	1094	7	0.01	2	1030	44	10	<20	28	<0.01	<10	9	<10	5	193
14	X09670	6.5	0.61	110	40	<5	0.85	5	7	110	1941	4.63	<10	0.49	914	9	0.01	2	1030	54	25	<20	25	<0.01	<10	8	<10	4	170
15	X09671	>30	0.22	790	30	<5	0.28	10	4	142	2264	3.19	<10	0.07	228	7	0.01	2	570	488	515	<20	19	<0.01	<10	5	<10	2	749
16	X09672	>30	0.31	205	30	<5	0.54	4	7	117	2091	3.37	<10	0.24	566	6	<0.01	2	720	128	105	<20	22	<0.01	<10	6	<10	3	174
17	X09673	3.0	0.95	45	45	<5	0.59	3	7	75	2688	4.34	<10	0.78	666	8	0.01	1	1040	14	5	<20	20	<0.01	<10	7	<10	3	138
18	X09674	<0.2	0.27	35	50	<5	0.42	6	9	109	6732	8.00	<10	0.09	255	14	0.02	<1	1080	46	5	<20	16	<0.01	<10	5	<10	2	40
19	X09675	1.7	0.94	20	50	<5	1.06	5	8	94	1630	4.25	<10	0.76	919	61	0.01	2	930	26	<5	<20	28	<0.01	<10	9	<10	3	216
20	X09676	1.9	1.67	20	65	<5	1.66	4	10	74	2449	4.72	<10	1.32	1533	6	0.01	1	1020	8	<5	<20	50	<0.01	<10	15	<10	5	157
21	X09677	2.8	1.04	30	50	<5	0.78	3	9	80	2462	4.12	<10	0.74	648	6	0.01	1	990	14	<5	<20	23	<0.01	<10	8	<10	4	145
22	X09678	4.1	0.54	55	40	<5	0.71	5	8	98	2632	4.63	<10	0.39	605	6	0.01	2	910	40	5	<20	21	<0.01	<10	5	<10	3	161
23	X09679	4.9	0.42	25	40	<5	0.49	3	8	117	2234	4.19	<10	0.28	407	6	0.01	2	790	66	5	<20	18	<0.01	<10	4	<10	2	62
24	X09680	7.6	0.25	40	35	<5	0.93	7	8	120	3164	4.12	<10	0.30	904	6	0.01	2	750	172	15	<20	31	<0.01	<10	5	<10	2	255
25	X09681	5.7	0.30	30	45	<5	1.49	4	8	127	3114	4.81	<10	0.56	1589	4	0.01	2	680	62	5	<20	44	<0.01	<10	5	<10	3	62

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09682	2.6	0.83	25	45	<5	1.62	3	7	86	1786	4.32	<10	0.95	1515	5	0.01	1	1100	18	<5	<20	41	<0.01	<10	8	<10	5	115
27	X09683	3.0	1.10	30	55	<5	0.92	4	17	52	2577	3.32	20	0.56	179	171	0.03	12	580	40	10	<20	60	0.04	<10	38	<10	8	229
28	X09684	2.5	0.92	25	50	<5	1.77	4	10	96	1590	5.40	<10	1.06	1971	6	0.01	1	960	14	<5	<20	43	<0.01	<10	9	<10	4	128
29	X09685	15.0	0.60	30	45	<5	0.95	4	9	118	3802	4.84	<10	0.46	1083	5	0.01	2	880	54	5	<20	32	<0.01	<10	5	<10	3	67
30	X09686	6.1	1.18	25	50	<5	1.41	3	9	101	3394	4.22	<10	1.00	1460	6	0.01	2	960	20	<5	<20	42	<0.01	<10	10	<10	4	91
31	X09687	1.6	1.32	25	65	<5	1.78	3	7	71	1853	3.97	<10	1.11	1358	7	<0.01	1	1000	6	<5	<20	52	<0.01	<10	11	<10	5	119
32	X09688	2.4	1.06	30	55	<5	1.14	3	8	87	2204	3.94	<10	0.76	919	7	<0.01	1	1030	28	<5	<20	35	<0.01	<10	8	<10	4	80
33	X09689	2.2	1.07	25	50	<5	0.98	3	7	87	3100	4.05	<10	0.80	1160	6	<0.01	1	1040	10	<5	<20	31	<0.01	<10	8	<10	4	100
34	X09690	2.5	0.32	20	40	<5	0.70	3	8	136	3027	4.30	<10	0.19	700	5	0.01	2	730	42	<5	<20	24	<0.01	<10	5	<10	2	20
35	X09691	1.7	1.75	25	85	<5	1.01	3	6	73	1615	4.04	<10	1.25	1091	8	<0.01	2	1030	6	<5	<20	35	<0.01	<10	13	<10	4	171
QC DATA:																													
Repeat:																													
1	X09657	5.0	0.49	85	40	<5	0.96	4	8	91	1659	4.25	<10	0.43	592	9	0.01	2	1060	30	15	<20	19	<0.01	<10	7	<10	4	112
10	X09666	>30	0.38	155	35	<5	0.46	6	6	104	2181	3.85	<10	0.20	343	7	0.01	2	970	216	90	<20	15	<0.01	<10	7	<10	4	271
19	X09675	1.9	0.91	20	45	<5	1.02	5	9	95	1622	4.28	<10	0.74	955	50	0.01	1	930	28	<5	<20	29	<0.01	<10	8	<10	3	227
Resplit:																													
1	X09657	5.6	0.48	85	40	<5	1.04	4	10	97	1762	3.86	<10	0.49	540	6	0.01	2	1000	32	15	<20	20	<0.01	<10	7	<10	4	101
Standard:																													
Pb113a		11.4	0.26	45	60	<5	1.65	36	2	<1	2243	0.99	<10	0.10	1532	62	0.01	<1	90	5494	10	<20	82	<0.01	<10	7	<10	1	6985

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/n5642
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5645

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

20-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07152
Submitted by: Peter Erwick

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09692	0.70	0.020
2	X09693	0.76	0.022
3	X09694	1.23	0.036
4	X09695	0.84	0.024
5	X09696	1.42	0.041
6	X09697	1.13	0.033
7	X09698	1.16	0.034
8	X09699	1.17	0.034
9	X09700	0.79	0.023
10	X09701	0.94	0.027
11	X09702	0.68	0.020
12	X09703	0.77	0.022
13	X09704	0.85	0.025
14	X09705	0.99	0.029
15	X09706	0.89	0.026
16	X09707	0.93	0.027
17	X09708	<0.03	<0.001
18	X09709	1.08	0.031
19	X09710	0.95	0.028
20	X09711	0.89	0.026
21	X09712	1.04	0.030
22	X09713	0.82	0.024
23	X09714	0.92	0.027
24	X09715	0.78	0.023
25	X09716	1.08	0.031

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5645 20-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X09717	3.10	0.090
27	X09718	0.78	0.023
28	X09719	1.09	0.032
29	X09720	0.81	0.024
30	X09721	1.40	0.041
31	X09722	1.67	0.049
32	X09723	1.18	0.034
33	X09724	0.80	0.023
34	X09725	1.15	0.034
35	X09726	1.18	0.034

QC DATA:

Repeat:

1	X09692	0.78	0.023
3	X09694	1.16	0.034
5	X09696	1.37	0.040
6	X09697	1.01	0.029
10	X09701	0.95	0.028
14	X09705	0.87	0.025
19	X09710	0.94	0.027
25	X09716	1.11	0.032
26	X09717	2.90	0.085
30	X09721	1.29	0.038
31	X09722	1.77	0.052

Resplits:

1	X09692	0.68	0.020

Standard:

OXi54		1.89	0.055

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

16-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5645

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07152
Submitted by: Peter Erwick

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09692	2.8	1.03	35	50	<5	1.24	3	7	45	1515	4.06	<10	0.72	849	9	<0.01	1	1130	16	<5	<20	39	<0.01	<10	10	<10	4	171
2	X09693	3.3	0.51	40	40	<5	0.83	3	8	65	2073	4.39	<10	0.43	693	6	0.01	<1	1060	28	<5	<20	28	<0.01	<10	4	<10	4	77
3	X09694	3.2	1.25	20	55	<5	0.87	3	8	72	2609	4.14	<10	0.77	743	7	0.01	1	940	16	<5	<20	31	<0.01	<10	9	<10	4	124
4	X09695	2.2	1.38	25	55	<5	1.99	3	8	65	1456	3.93	<10	1.00	1605	8	0.01	1	990	8	<5	<20	80	<0.01	<10	12	<10	5	133
5	X09696	4.1	1.07	25	45	<5	1.34	4	8	84	2709	4.25	<10	0.79	1237	8	0.01	1	950	16	<5	<20	53	<0.01	<10	11	<10	4	129
6	X09697	3.3	0.77	50	40	<5	0.72	3	7	80	2032	4.40	<10	0.45	510	9	0.01	<1	1040	18	<5	<20	31	<0.01	<10	6	<10	3	74
7	X09698	2.5	0.78	55	45	<5	1.46	3	6	87	1465	3.77	<10	0.63	1056	10	<0.01	1	940	18	<5	<20	55	<0.01	<10	9	<10	4	86
8	X09699	2.8	0.71	50	40	<5	1.47	3	7	80	1656	3.70	<10	0.59	1042	7	<0.01	1	920	16	5	<20	53	<0.01	<10	8	<10	4	77
9	X09700	3.0	1.11	20	50	<5	1.45	3	7	107	3084	3.86	<10	0.86	1105	7	0.01	2	960	32	<5	<20	62	<0.01	<10	12	<10	4	95
10	X09701	2.9	1.55	20	70	<5	1.30	3	7	103	2166	3.87	<10	0.99	1030	9	<0.01	2	1000	10	<5	<20	55	<0.01	<10	12	<10	4	215
11	X09702	3.8	0.90	25	40	<5	0.68	4	7	86	1950	4.11	<10	0.59	584	9	<0.01	1	1070	14	<5	<20	33	<0.01	<10	6	<10	3	195
12	X09703	5.5	0.28	35	35	<5	0.47	5	7	136	2787	4.28	<10	0.09	333	6	<0.01	2	860	46	<5	<20	25	<0.01	<10	3	<10	2	42
13	X09704	5.7	0.40	20	35	<5	0.29	4	9	118	3182	4.02	<10	0.15	173	7	0.01	2	990	34	<5	<20	14	<0.01	<10	5	<10	3	75
14	X09705	5.2	0.30	35	40	<5	0.27	4	9	126	2482	4.77	<10	0.04	120	5	0.01	2	1010	28	<5	<20	14	<0.01	<10	4	<10	2	30
15	X09706	4.0	0.36	40	35	<5	0.25	4	8	113	2521	4.43	<10	0.08	116	6	0.01	2	970	40	5	<20	14	<0.01	<10	6	<10	3	75
16	X09707	3.4	0.64	20	40	<5	0.30	7	8	112	2520	3.94	<10	0.32	241	8	<0.01	2	1030	30	<5	<20	16	<0.01	<10	5	<10	4	231
17	X09708	<0.2	0.97	5	220	<5	0.58	1	6	88	6	2.02	<10	0.52	488	<1	0.08	6	840	8	<5	<20	92	0.13	<10	39	<10	4	38
18	X09709	3.9	1.32	25	55	<5	0.25	3	7	129	2917	4.77	<10	0.76	367	6	0.01	2	910	12	<5	<20	14	<0.01	<10	11	<10	3	107
19	X09710	2.2	0.88	15	50	<5	0.35	2	7	115	2203	2.90	<10	0.50	345	11	<0.01	3	990	8	<5	<20	21	<0.01	<10	7	<10	3	71
20	X09711	2.4	0.84	30	40	<5	0.50	3	9	90	2322	3.77	<10	0.50	431	16	<0.01	2	1050	10	<5	<20	21	<0.01	<10	7	<10	3	67
21	X09712	3.6	1.02	60	70	10	0.65	5	13	51	3291	3.59	20	0.44	242	207	0.02	15	370	110	30	<20	40	0.03	<10	33	<10	8	139
22	X09713	3.3	0.23	50	35	<5	0.61	4	8	106	2398	4.20	<10	0.08	417	9	<0.01	1	950	54	10	<20	29	<0.01	<10	4	<10	3	25
23	X09714	3.8	0.38	40	40	<5	0.82	4	8	103	2873	4.16	<10	0.21	560	7	0.01	2	890	44	10	<20	39	<0.01	<10	4	<10	2	31
24	X09715	4.8	0.26	30	35	<5	0.68	4	8	125	2796	4.00	<10	0.13	483	6	0.01	2	800	68	10	<20	35	<0.01	<10	4	<10	2	12
25	X09716	3.7	0.84	100	45	<5	1.05	3	9	94	2131	3.76	<10	0.61	912	6	<0.01	2	920	20	10	<20	42	<0.01	<10	6	<10	4	75

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09717	4.2	0.71	200	45	<5	1.29	5	10	91	1428	5.44	<10	0.62	1355	5	<0.01	<1	1050	28	10	<20	43	<0.01	<10	6	<10	4	88
27	X09718	4.1	0.28	30	35	<5	0.43	3	9	147	2542	3.66	<10	0.07	244	9	0.01	3	840	42	10	<20	31	<0.01	<10	3	<10	2	22
28	X09719	4.0	0.42	20	35	<5	0.73	3	8	90	3521	3.77	<10	0.28	565	6	<0.01	1	1000	26	<5	<20	35	<0.01	<10	3	<10	2	50
29	X09720	2.8	0.30	10	35	<5	0.92	3	9	86	3106	3.49	<10	0.19	626	11	<0.01	1	1030	32	<5	<20	44	<0.01	<10	2	<10	2	16
30	X09721	2.6	1.06	15	45	<5	1.54	3	9	65	3642	3.81	<10	0.73	1361	5	<0.01	<1	930	10	<5	<20	105	<0.01	<10	9	<10	3	47
31	X09722	2.7	1.14	15	55	<5	1.80	3	9	112	4252	4.36	<10	0.74	1392	5	0.01	1	800	8	<5	<20	86	<0.01	<10	11	<10	2	37
32	X09723	1.8	1.41	15	55	<5	0.97	3	7	100	2303	4.54	<10	0.78	824	5	0.01	<1	980	6	<5	<20	41	<0.01	<10	11	<10	2	56
33	X09724	1.7	0.60	25	40	<5	0.76	3	7	109	2139	3.41	<10	0.36	580	5	<0.01	2	900	18	10	<20	29	<0.01	<10	5	<10	2	34
34	X09725	2.1	0.73	45	45	<5	1.05	3	6	89	2645	3.93	<10	0.60	919	4	<0.01	<1	870	12	5	<20	32	<0.01	<10	6	<10	2	67
35	X09726	3.2	0.83	25	45	<5	0.64	4	9	102	3970	4.69	<10	0.45	573	6	0.01	1	840	18	<5	<20	27	<0.01	<10	8	<10	2	45
QC DATA:																													
Repeat:																													
1	X09692	2.4	1.11	40	50	<5	1.27	3	8	48	1562	4.11	<10	0.73	886	13	<0.01	1	1170	14	<5	<20	41	<0.01	<10	8	<10	5	174
10	X09701	2.7	1.54	20	65	<5	1.28	3	7	102	2147	3.90	<10	1.03	1004	9	<0.01	2	990	8	<5	<20	55	<0.01	<10	12	<10	4	212
19	X09710	2.3	0.91	15	45	<5	0.38	2	7	118	2223	2.91	<10	0.50	349	10	<0.01	3	1010	8	<5	<20	22	<0.01	10	7	<10	3	71
Resplit:																													
1	X09692	2.9	1.08	35	50	<5	1.30	3	8	49	1527	3.90	<10	0.71	886	13	<0.01	1	1160	12	<5	<20	39	<0.01	<10	7	<10	4	166
Standard:																													
PB113A		11.1	0.25	40	60	<5	1.68	36	2	<1	2299	0.95	<10	0.10	1488	60	0.01	<1	90	5468	10	<20	89	<0.01	<10	6	<10	1	6903

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/n5642
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5646

Revised

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

20-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07153
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	X05168	1.02	0.030		
2	X05169	0.60	0.017		
3	X05170	0.70	0.020		
4	X05171	0.98	0.029		
5	X05172	0.72	0.021		
6	X05173	1.07	0.031		
7	X05174	0.69	0.020		
8	X05175	0.86	0.025		
9	X05176	0.61	0.018		
10	X05177	0.64	0.019		
11	X05178	0.94	0.027		
12	X05179	0.54	0.016		
13	X05180	0.88	0.026		
14	X05181	1.04	0.030		
15	X05182	0.63	0.018		
16	X05183	0.88	0.026		
17	X05184	1.02	0.030		
18	X05185	2.16	0.063		
19	X05186	1.52	0.044	36.9	1.076
20	X05187	0.63	0.018		
21	X05188	1.30	0.038		
22	X05189	0.90	0.026		
23	X05190	0.83	0.024	152	4.433
24	X05191	0.91	0.027		
25	X05192	0.75	0.022		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5646

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
26	X05193	1.12	0.033		
27	X05194	0.80	0.023		
28	X05195	0.90	0.026		
29	X05196	0.95	0.028		
30	X05197	0.86	0.025		
31	X05198	0.57	0.017		
32	X05199	0.79	0.023		
33	X05200	<0.03	<0.001		
34	X05201	0.85	0.025		
35	X05202	0.86	0.025		
QC DATA:					
Repeat:					
1	X05168	1.10	0.032		
6	X05173	1.07	0.031		
10	X05177	0.58	0.017		
18	X05185	1.99	0.058		
19	X05186	1.61	0.047		
21	X05188	1.18	0.034		
23	X05190			152	4.433
26	X05193	1.02	0.030		
Resplits:					
1	X05168	1.14	0.033		
Standard:					
OXi54		1.88	0.055		
Pb113				22.9	0.668

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
XLS/07

16-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5646

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07153
Submitted by: Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05168	5.0	0.74	10	45	<5	0.64	3	8	97	3994	4.01	<10	0.46	396	7	0.02	1	960	70	<5	<20	28	<0.01	<10	15	<10	2	80
2	X05169	2.6	0.65	15	45	<5	1.12	3	6	119	1863	3.06	<10	0.41	627	7	0.01	2	840	52	<5	<20	33	<0.01	<10	7	<10	2	110
3	X05170	2.3	0.80	10	45	<5	0.61	2	6	93	1768	3.04	<10	0.53	328	9	0.02	1	970	22	<5	<20	35	<0.01	<10	14	<10	2	80
4	X05171	4.7	0.42	15	35	<5	0.27	5	10	158	3288	4.53	<10	0.16	163	8	0.01	2	770	50	<5	<20	11	<0.01	<10	5	<10	2	141
5	X05172	3.5	0.34	10	35	<5	1.52	3	6	161	2916	3.07	<10	0.13	705	9	0.01	2	550	56	<5	<20	49	<0.01	<10	6	<10	4	65
6	X05173	4.1	0.59	10	35	<5	0.47	3	8	174	3589	4.08	<10	0.41	316	9	0.01	2	680	24	<5	<20	30	<0.01	<10	8	<10	2	87
7	X05174	2.6	0.55	10	30	<5	0.78	4	7	134	2065	3.47	<10	0.41	514	11	0.02	2	720	50	<5	<20	36	<0.01	<10	10	<10	2	96
8	X05175	2.1	0.81	10	35	<5	1.17	4	9	185	2268	4.41	<10	0.41	640	14	0.02	1	850	52	<5	<20	83	<0.01	<10	12	<10	2	82
9	X05176	2.4	0.45	10	30	<5	0.71	4	9	153	2682	3.91	<10	0.33	491	7	0.02	2	810	66	<5	<20	32	<0.01	<10	9	<10	2	89
10	X05177	1.9	0.67	10	35	<5	0.71	3	7	137	1776	4.41	<10	0.48	507	10	0.02	1	890	32	<5	<20	27	<0.01	<10	11	<10	2	74
11	X05178	2.4	0.68	10	40	<5	0.88	3	10	179	2581	4.06	<10	0.51	693	11	0.02	3	700	24	<5	<20	35	<0.01	<10	11	<10	2	66
12	X05179	2.5	0.75	15	40	<5	0.61	3	4	123	1974	3.89	<10	0.51	557	12	0.02	<1	800	28	<5	<20	20	<0.01	<10	11	<10	2	65
13	X05180	2.1	0.47	5	35	<5	2.57	3	5	110	1971	3.82	<10	0.39	658	8	0.02	<1	810	16	<5	<20	336	<0.01	<10	10	<10	3	36
14	X05181	3.6	1.07	65	60	5	0.68	5	14	60	3275	3.71	20	0.45	267	206	0.03	16	580	104	30	<20	43	0.03	<10	35	<10	8	150
15	X05182	2.7	0.40	5	35	<5	1.31	3	9	126	2402	4.24	<10	0.36	791	16	0.02	<1	790	40	<5	<20	79	<0.01	<10	7	<10	2	36
16	X05183	3.2	0.44	5	40	<5	1.99	3	10	115	2651	4.25	<10	0.33	644	8	0.02	<1	800	52	<5	<20	305	<0.01	<10	7	<10	2	64
17	X05184	1.6	0.69	5	40	<5	2.28	3	5	143	1686	3.81	<10	0.37	403	11	0.02	<1	930	18	<5	<20	433	<0.01	<10	20	<10	3	62
18	X05185	5.4	0.25	5	40	<5	1.50	4	12	111	5277	5.03	<10	0.25	588	5	0.02	<1	820	40	<5	<20	253	<0.01	<10	7	<10	2	20
19	X05186	>30	0.36	25	35	<5	0.90	6	12	130	5202	4.47	<10	0.26	690	8	0.02	1	720	120	25	<20	84	<0.01	<10	6	<10	2	216
20	X05187	18.0	0.32	10	40	<5	1.21	4	9	138	3156	4.35	<10	0.29	1703	7	0.01	1	890	36	5	<20	54	<0.01	<10	5	<10	3	105
21	X05188	4.2	0.53	5	45	<5	1.70	3	6	136	3330	4.03	<10	0.41	804	5	0.02	1	780	24	<5	<20	127	<0.01	<10	10	<10	3	37
22	X05189	10.7	0.37	20	35	<5	0.87	3	7	115	3134	4.76	<10	0.19	522	5	0.01	<1	910	24	<5	<20	64	<0.01	<10	6	<10	2	46
23	X05190	>30	0.25	295	40	20	0.18	8	9	202	3886	5.49	<10	0.05	124	11	0.02	2	670	196	430	<20	11	<0.01	<10	6	<10	1	412
24	X05191	2.2	0.43	20	40	<5	0.47	6	14	114	1149	6.37	<10	0.08	168	54	0.02	3	2420	52	<5	<20	23	<0.01	<10	16	<10	4	264
25	X05192	3.5	0.44	40	35	<5	0.40	4	15	146	2626	5.82	<10	0.11	228	73	0.02	4	1910	116	15	<20	38	<0.01	<10	15	<10	2	173

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05193	2.1	0.48	15	35	<5	0.36	4	15	155	1730	5.12	<10	0.12	212	72	0.02	4	1730	72	<5	<20	24	<0.01	<10	14	<10	2	160
27	X05194	1.9	0.42	5	25	<5	0.28	3	11	140	1528	3.30	<10	0.13	234	53	0.02	3	1230	60	<5	<20	19	<0.01	<10	9	<10	2	212
28	X05195	1.7	0.38	10	30	<5	0.42	4	11	163	1688	4.36	<10	0.07	166	42	0.02	6	2000	48	<5	<20	38	<0.01	<10	11	<10	3	255
29	X05196	1.8	0.40	10	30	<5	0.38	6	13	163	1849	5.00	<10	0.08	140	53	0.02	7	1790	74	<5	<20	80	<0.01	<10	8	<10	2	431
30	X05197	2.3	0.39	10	30	<5	0.39	4	13	136	1933	4.69	<10	0.07	123	71	0.02	6	1820	64	<5	<20	56	<0.01	<10	7	<10	2	171
31	X05198	2.5	0.33	5	25	<5	0.16	13	11	198	1894	4.29	<10	0.08	147	86	0.02	7	710	154	<5	<20	134	<0.01	<10	5	<10	<1	1222
32	X05199	2.1	0.33	35	25	<5	0.20	7	10	212	1978	3.87	<10	0.06	79	123	0.02	8	920	122	10	<20	50	<0.01	<10	5	<10	1	555
33	X05200	<0.2	0.99	5	270	<5	0.65	1	7	108	5	2.17	<10	0.51	568	1	0.09	7	940	6	<5	<20	98	0.15	<10	38	<10	5	46
34	X05201	2.3	0.34	10	25	<5	0.26	9	10	133	1770	4.08	<10	0.05	75	123	0.02	8	1230	110	<5	<20	29	<0.01	<10	5	<10	2	763
35	X05202	2.1	0.33	10	25	<5	0.17	5	11	175	1758	4.13	<10	0.06	80	58	0.02	8	810	80	<5	<20	37	<0.01	<10	4	<10	<1	345
QC DATA:																													
Repeat:																													
1	X05168	4.9	0.73	10	45	<5	0.65	3	8	97	3961	3.97	<10	0.45	400	7	0.02	1	930	68	<5	<20	27	<0.01	<10	14	<10	2	81
10	X05177	1.9	0.76	10	35	<5	0.77	4	8	147	1780	4.46	<10	0.46	513	11	0.02	1	1010	33	<5	<20	28	<0.01	<10	11	<10	2	79
19	X05186	>30	0.36	25	35	<5	0.89	6	12	129	5250	4.49	<10	0.26	672	5	0.02	1	740	120	25	<20	86	<0.01	<10	6	<10	2	215
Resplit:																													
1	X05168	4.1	0.78	10	50	<5	0.91	2	6	129	2968	3.60	<10	0.46	537	8	0.02	2	960	68	<5	<20	27	<0.01	<10	16	<10	2	84
Standard:																													
Pb113A		11.5	0.26	45	70	<5	1.11	43	2	2	2277	1.03	<10	0.10	1508	69	0.01	<1	90	5478	5	<20	82	0.01	<10	5	<10	1	6912

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/n5646
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5647

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

14-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07154
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	X09727	1.27	0.037		
2	X09728	1.23	0.036		
3	X09729	0.69	0.020		
4	X09730	0.85	0.025		
5	X09731	0.65	0.019		
6	X09732	0.87	0.025		
7	X09733	0.61	0.018		
8	X09734	0.82	0.024		
9	X09735	<0.03	<0.001		
10	X09736	1.06	0.031		
11	X09737	0.93	0.027		
12	X09738	0.84	0.024		
13	X09739	1.89	0.055		
14	X09740	0.61	0.018		
15	X09741	1.44	0.042		
16	X09742	0.98	0.029		
17	X09743	1.06	0.031		
18	X09744	1.11	0.032		
19	X09745	0.63	0.018		
20	X09746	0.76	0.022		
21	X09747	0.79	0.023		
22	X09748	0.61	0.018		
23	X09749	0.48	0.014		
24	X09750	1.54	0.045		
25	X09751	1.04	0.030		
26	X09752	1.06	0.031		
27	X09753	0.61	0.018		
28	X09754	1.08	0.031		
29	X09755	1.45	0.042		

Lynn Brace /pes
ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5647 14-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
30	X09756	1.10	0.032		
31	X09757	1.56	0.045		
32	X09758	1.04	0.030		
33	X09759	3.20	0.093	114	3.33
34	X09760	23.5	0.685	237	6.91
35	X09761	1.10	0.032	68.8	2.01
QC DATA:					
Repeat:					
1	X09727	1.18	0.034		
2	X09728	1.22	0.036		
10	X09736	0.99	0.029		
19	X09745	0.63	0.018		
33	X09759	3.10	0.090		
34	X09760	24.4	0.712		
35	X09761	1.18	0.034		
Standard:					
OXi54		1.83	0.053		
Pb113				22.4	0.65

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

26-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5647

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07154
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09727	1.7	1.67	20	65	<5	0.49	2	9	82	2911	4.84	<10	0.86	621	9	0.02	<1	960	8	<5	<20	20	<0.01	<10	14	<10	2	91
2	X09728	2.0	1.00	90	50	<5	0.58	2	9	88	2552	4.47	<10	0.53	508	7	0.02	<1	1140	16	5	<20	18	<0.01	<10	8	<10	3	59
3	X09729	1.5	0.43	30	40	<5	0.70	2	8	110	1688	4.58	<10	0.28	478	11	0.02	<1	1030	20	<5	<20	21	<0.01	<10	6	<10	2	36
4	X09730	2.0	0.43	15	45	<5	1.08	2	9	82	2631	4.03	<10	0.35	689	7	0.02	<1	960	14	<5	<20	32	<0.01	<10	5	<10	2	29
5	X09731	2.2	0.30	20	35	<5	0.81	3	8	90	1798	4.57	<10	0.17	451	8	0.02	<1	1000	34	5	<20	29	<0.01	<10	6	<10	2	15
6	X09732	1.0	1.31	40	65	<5	1.32	2	7	85	1372	3.79	<10	0.88	945	9	0.02	<1	1190	10	<5	<20	40	<0.01	<10	11	<10	4	68
7	X09733	1.2	1.78	15	140	<5	1.75	2	6	73	1902	3.97	<10	1.25	1424	8	0.02	<1	1050	6	<5	<20	59	<0.01	<10	17	<10	5	100
8	X09734	1.2	2.22	25	70	<5	1.21	3	8	88	1895	5.95	<10	1.40	1148	4	0.02	<1	1160	12	<5	<20	43	<0.01	<10	22	<10	4	108
9	X09735	0.2	1.10	10	270	<5	0.63	<1	6	98	4	2.18	<10	0.58	557	<1	0.11	7	960	4	<5	<20	92	0.14	<10	41	<10	5	49
10	X09736	1.3	1.06	35	45	<5	0.81	2	10	95	2010	4.91	<10	0.62	603	7	0.02	<1	1170	14	<5	<20	30	<0.01	<10	10	<10	3	55
11	X09737	1.5	1.20	25	55	<5	1.20	2	8	128	2191	4.33	<10	0.76	894	12	0.02	1	970	14	<5	<20	43	<0.01	<10	13	<10	3	67
12	X09738	1.7	0.95	30	45	<5	1.46	2	8	95	1916	4.20	<10	0.68	1105	5	0.02	<1	1020	26	<5	<20	46	<0.01	<10	10	<10	3	73
13	X09739	4.1	1.08	35	50	<5	0.97	3	18	61	8611	4.04	20	0.56	201	581	0.05	63	610	56	20	<20	62	0.04	<10	36	<10	7	77
14	X09740	3.3	0.35	25	40	<5	1.03	2	8	104	2758	4.32	<10	0.27	760	8	0.02	<1	850	62	5	<20	38	<0.01	<10	6	<10	2	22
15	X09741	4.3	0.40	35	35	<5	0.87	4	9	156	2624	4.97	<10	0.30	804	7	0.02	2	880	58	5	<20	32	<0.01	<10	6	<10	2	143
16	X09742	3.7	0.88	70	40	<5	0.57	2	8	97	2178	3.90	<10	0.55	659	8	0.02	1	1210	24	5	<20	20	<0.01	<10	10	<10	4	150
17	X09743	3.2	1.08	35	50	<5	0.66	2	8	100	2325	4.30	<10	0.70	879	8	0.02	1	1030	22	<5	<20	22	<0.01	<10	11	<10	4	118
18	X09744	2.6	1.38	40	50	<5	0.83	2	10	109	2406	5.14	<10	0.84	989	7	0.02	1	1020	12	<5	<20	29	<0.01	<10	14	<10	4	94
19	X09745	1.4	1.30	25	60	<5	1.06	2	6	111	1551	3.99	<10	0.90	1114	6	0.02	1	1080	12	<5	<20	36	<0.01	<10	12	<10	4	100
20	X09746	1.4	1.00	20	50	<5	1.16	2	7	68	1664	3.69	<10	0.77	1014	11	0.02	<1	1220	14	<5	<20	33	<0.01	<10	10	<10	4	88
21	X09747	1.9	1.03	10	65	<5	2.26	2	6	89	2820	3.57	<10	1.03	1703	5	0.02	2	1130	18	<5	<20	62	<0.01	<10	11	<10	5	64
22	X09748	1.1	1.66	15	85	<5	3.34	2	5	59	1289	3.90	<10	1.25	1611	5	0.02	<1	1090	10	<5	<20	757	<0.01	<10	15	<10	5	99
23	X09749	1.1	1.38	10	60	<5	2.56	2	7	66	952	3.83	<10	1.07	1554	12	0.02	<1	1160	16	<5	<20	437	<0.01	<10	13	<10	4	112
24	X09750	2.8	1.16	70	50	<5	1.72	2	6	104	2165	4.28	<10	0.81	927	6	0.02	1	1030	20	<5	<20	200	<0.01	<10	12	<10	4	121
25	X09751	2.2	1.95	25	80	<5	2.45	2	7	94	2541	4.86	<10	1.32	1117	4	0.02	<1	1080	12	<5	<20	1151	<0.01	<10	19	<10	4	161

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09752	1.8	1.47	15	50	<5	2.40	2	8	86	1995	4.89	<10	1.08	1230	6	0.02	<1	1100	16	<5	<20	252	<0.01	<10	14	<10	5	118
27	X09753	1.4	1.72	15	100	<5	1.81	2	6	96	1495	4.22	<10	1.06	1250	7	0.02	1	1120	12	<5	<20	79	<0.01	<10	16	<10	4	110
28	X09754	3.0	1.31	50	45	<5	0.66	2	8	154	2750	5.04	<10	0.68	582	5	0.02	2	1040	22	<5	<20	27	<0.01	<10	12	<10	2	126
29	X09755	4.4	1.41	25	45	<5	0.75	3	9	99	3724	5.75	<10	0.76	715	8	0.02	<1	950	18	<5	<20	35	<0.01	<10	14	<10	3	132
30	X09756	3.3	0.49	160	30	<5	1.02	2	7	99	1560	4.17	<10	0.20	556	12	0.02	1	1250	18	<5	<20	34	<0.01	<10	6	<10	3	62
31	X09757	4.2	0.46	155	30	<5	0.80	2	8	104	1998	4.65	<10	0.18	444	10	0.02	1	1110	22	5	<20	32	<0.01	<10	5	<10	3	55
32	X09758	10.5	0.82	100	40	<5	0.44	3	8	132	1584	5.78	<10	0.50	481	13	0.02	<1	950	64	5	<20	18	<0.01	<10	9	<10	2	177
33	X09759	>30	0.25	400	40	5	0.17	10	5	144	2276	8.30	<10	0.02	66	4	0.03	<1	850	502	65	<20	10	<0.01	<10	4	<10	1	740
34	X09760	>30	0.22	500	40	<5	0.12	8	2	140	2649	6.07	<10	0.02	36	4	0.02	<1	610	824	160	<20	7	<0.01	<10	3	<10	<1	682
35	X09761	>30	0.18	480	30	10	0.12	6	4	169	1760	4.73	<10	0.03	88	10	0.02	<1	500	182	130	<20	9	<0.01	<10	3	<10	<1	369
QC DATA:																													
Repeat:																													
1	X09727	1.9	1.71	20	70	<5	0.47	2	9	88	2924	5.06	<10	0.88	639	9	0.02	<1	990	8	<5	<20	20	<0.01	<10	16	<10	2	97
10	X09736	1.5	1.09	35	45	<5	0.83	2	10	100	2027	4.93	<10	0.62	620	6	0.02	<1	1210	16	<5	<20	30	<0.01	<10	11	<10	3	58
19	X09745	1.5	1.31	20	55	<5	1.07	2	6	115	1534	4.03	<10	0.92	1127	6	0.02	2	1090	14	<5	<20	37	<0.01	<10	12	<10	4	99
Resplit:																													
1	X09727	1.9	1.57	20	70	<5	0.53	2	7	94	2829	4.71	<10	0.83	630	14	0.02	<1	1030	10	<5	<20	23	<0.01	<10	15	<10	2	92
Standard:																													
PB113A		11.2	0.27	55	75	<5	1.73	42	2	2	2411	1.04	<10	0.11	1457	59	0.02	1	100	5582	5	<20	108	0.01	<10	8	<10	1	7114

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
dl/n5647S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5651

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

20-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07155
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05203	0.62	0.018
2	X05204	0.83	0.024
3	X05205	0.76	0.022
4	X05206	0.80	0.023
5	X05207	0.63	0.018
6	X05208	1.12	0.033
7	X05209	0.57	0.017
8	X05210	0.96	0.028
9	X05211	0.68	0.020
10	X05212	0.51	0.015
11	X05213	0.56	0.016
12	X05214	0.49	0.014
13	X05215	0.51	0.015
14	X05216	1.27	0.037
15	X05217	1.35	0.039
16	X05218	1.26	0.037
17	X05219	1.29	0.038
18	X05220	1.06	0.031
19	X05221	0.84	0.024
20	X05222	0.68	0.020
21	X05223	1.10	0.032
22	X05224	0.84	0.024
23	X05225	1.42	0.041
24	X05226	1.87	0.055
25	X05227	1.27	0.037
26	X05228	1.51	0.044

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7 - 5651

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	X05229	0.88	0.026
28	X05230	1.41	0.041
29	X05231	0.64	0.019
30	X05232	0.91	0.027
31	X05233	1.11	0.032
32	X05234	1.23	0.036
33	X05235	<0.03	<0.001
34	X05236	1.43	0.042
35	X05237	0.88	0.026
QC DATA:			
Repeat:			
1	X05203	0.60	0.017
2	X05204	0.90	0.026
10	X05212	0.48	0.014
15	X05217	1.28	0.037
16	X05218	1.43	0.042
19	X05221	0.92	0.027
28	X05230	1.36	0.040
Resplits:			
1	X05203	0.69	0.020
Standard:			
OXK48		3.49	0.102

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
XLS/07

20-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5651

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1


No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07155
Submitted by: Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05203	2.3	0.35	10	25	<5	0.24	3	11	154	1611	4.11	<10	0.08	108	52	0.02	8	1160	66	<5	<20	31	<0.01	<10	5	<10	1	242
2	X05204	2.8	0.50	15	30	<5	0.25	4	11	156	1373	5.64	<10	0.10	196	44	0.03	10	1150	46	<5	<20	32	<0.01	<10	7	<10	1	315
3	X05205	3.4	0.32	15	25	<5	0.17	5	11	157	1591	5.25	<10	0.08	112	36	0.02	9	870	170	<5	<20	31	<0.01	<10	4	<10	<1	447
4	X05206	2.3	0.29	10	25	<5	0.14	3	11	162	1650	4.18	<10	0.04	70	57	0.03	9	630	70	<5	<20	19	<0.01	<10	3	<10	<1	152
5	X05207	2.1	0.26	10	25	<5	0.12	2	11	139	1753	4.29	<10	0.04	70	42	0.02	9	560	46	<5	<20	17	<0.01	<10	3	<10	<1	124
6	X05208	2.6	0.32	10	25	<5	0.16	6	11	159	1574	5.07	<10	0.06	117	117	0.03	9	780	78	<5	<20	20	<0.01	<10	5	<10	1	766
7	X05209	1.9	0.24	5	25	<5	0.08	3	11	111	1688	4.89	<10	0.04	65	60	0.02	7	420	44	<5	<20	22	<0.01	<10	3	<10	<1	138
8	X05210	1.8	0.28	10	25	<5	0.12	3	12	148	1925	4.62	<10	0.03	52	69	0.02	9	620	40	<5	<20	42	<0.01	<10	4	<10	2	172
9	X05211	1.5	0.34	10	30	<5	0.43	3	11	117	1964	5.13	<10	0.08	301	87	0.02	3	1930	84	<5	<20	31	<0.01	<10	5	<10	3	253
10	X05212	1.4	0.37	10	30	<5	0.44	5	12	124	2036	5.13	<10	0.08	336	76	0.02	3	1900	88	<5	<20	40	<0.01	<10	6	<10	2	387
11	X05213	2.1	0.31	65	25	<5	0.34	2	9	141	2267	4.00	<10	0.07	229	57	0.02	5	1460	104	40	<20	52	<0.01	<10	5	<10	2	102
12	X05214	2.0	0.26	65	30	5	0.25	4	12	145	1296	5.97	<10	0.02	67	77	0.03	5	1150	96	45	<20	59	<0.01	<10	4	<10	1	190
13	X05215	2.1	0.29	20	35	10	0.44	8	16	159	1561	7.71	<10	0.02	83	58	0.03	8	2150	158	<5	<20	64	<0.01	<10	4	<10	2	687
14	X05216	1.0	0.26	10	30	<5	0.23	2	12	176	1859	4.82	<10	0.01	53	73	0.02	5	1060	30	<5	<20	51	<0.01	<10	4	<10	1	56
15	X05217	0.6	0.29	10	30	<5	0.36	2	11	144	1614	4.66	<10	0.02	61	70	0.02	3	1680	20	<5	<20	57	<0.01	<10	5	<10	2	85
16	X05218	1.3	0.29	20	30	<5	0.37	3	12	150	1687	5.44	<10	<0.01	63	83	0.03	3	1790	28	<5	<20	56	<0.01	<10	6	<10	2	147
17	X05219	1.0	0.32	15	30	<5	0.36	3	12	119	1710	5.89	<10	0.04	73	49	0.02	2	1740	26	<5	<20	58	<0.01	<10	5	<10	2	98
18	X05220	1.1	0.29	10	30	<5	0.29	3	9	142	1657	5.70	<10	0.03	52	42	0.03	2	1290	30	<5	<20	53	<0.01	<10	5	<10	2	224
19	X05221	1.1	0.25	10	30	<5	0.12	2	12	123	1792	5.05	<10	0.03	62	59	0.02	2	450	42	<5	<20	50	<0.01	<10	4	<10	1	70
20	X05222	1.1	0.34	10	25	<5	0.20	4	10	147	1696	4.46	<10	0.04	65	62	0.03	3	830	74	<5	<20	46	<0.01	<10	5	<10	2	428
21	X05223	1.1	0.24	10	25	<5	0.11	2	8	180	1653	4.43	<10	0.02	54	82	0.02	3	460	40	<5	<20	38	<0.01	<10	4	<10	1	102
22	X05224	1.2	0.25	15	30	<5	0.08	2	14	170	2123	5.27	<10	0.01	39	70	0.02	3	330	32	<5	<20	35	<0.01	<10	4	<10	<1	21
23	X05225	2.1	0.36	170	25	<5	0.16	2	14	169	2000	4.92	<10	0.09	68	84	0.02	3	630	94	80	<20	40	<0.01	<10	6	<10	<1	98
24	X05226	3.9	1.03	35	40	<5	0.97	3	18	52	8563	4.02	20	0.57	204	542	0.04	57	580	46	25	<20	56	0.04	<10	35	<10	7	67
25	X05227	2.2	0.35	90	30	<5	0.15	2	13	219	2107	5.61	<10	0.03	62	101	0.03	5	560	48	55	<20	41	<0.01	<10	6	<10	1	78

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05228	1.3	0.27	20	30	<5	0.23	2	14	117	1754	5.36	<10	0.02	74	125	0.02	2	1010	32	5	<20	37	<0.01	<10	5	<10	3	45
27	X05229	1.2	0.25	15	30	<5	0.17	2	13	130	1653	6.63	<10	0.02	80	162	0.02	2	780	26	<5	<20	34	<0.01	<10	5	<10	2	36
28	X05230	1.2	0.28	10	30	<5	0.13	2	12	150	1866	5.78	<10	0.04	89	55	0.02	2	430	22	<5	<20	40	<0.01	<10	5	<10	1	48
29	X05231	1.0	0.31	20	30	<5	0.24	3	12	198	1521	5.95	<10	0.02	59	53	0.02	3	1080	44	<5	<20	31	<0.01	<10	6	<10	1	72
30	X05232	1.1	0.27	15	30	<5	0.29	3	13	132	1543	6.52	<10	0.03	80	54	0.02	<1	1320	32	<5	<20	32	<0.01	<10	5	<10	2	83
31	X05233	1.0	0.27	35	30	<5	0.21	2	12	206	1720	5.89	<10	0.01	82	58	0.02	3	950	42	<5	<20	26	<0.01	<10	6	<10	1	81
32	X05234	1.0	0.24	35	30	<5	0.23	2	12	177	1762	5.94	<10	0.01	68	66	0.02	2	1010	40	<5	<20	26	<0.01	<10	4	<10	1	87
33	X05235	<0.2	1.03	10	245	<5	0.50	<1	7	107	7	2.23	<10	0.58	566	<1	0.09	6	940	8	<5	<20	84	0.14	<10	40	<10	4	46
34	X05236	0.9	0.33	25	30	<5	0.27	2	10	175	1367	6.20	<10	0.06	115	69	0.02	3	1270	32	<5	<20	25	<0.01	<10	6	<10	1	36
35	X05237	0.9	0.33	10	30	<5	0.28	2	11	163	1332	4.91	<10	0.10	195	51	0.02	2	1290	30	<5	<20	21	<0.01	<10	6	<10	1	45
QC DATA:																													
Repeat:																													
1	X05203	2.2	0.32	10	25	<5	0.26	3	11	147	1584	4.01	<10	0.07	102	58	0.02	8	1140	64	<5	<20	28	<0.01	<10	5	<10	1	236
10	X05212	1.4	0.33	10	30	<5	0.43	5	11	118	1964	5.09	<10	0.07	324	77	0.02	3	1850	86	<5	<20	39	<0.01	<10	6	<10	2	385
19	X05221	1.1	0.23	10	25	<5	0.12	2	12	117	1782	5.03	<10	0.03	60	58	0.02	2	440	40	<5	<20	50	<0.01	<10	4	<10	1	68
Resplit:																													
1	X05203	2.6	0.34	10	25	<5	0.27	4	12	163	1695	4.36	<10	0.07	103	58	0.02	8	1210	64	<5	<20	30	<0.01	<10	5	<10	1	259
Standard:																													
Pb113		11.4	0.25	45	50	<5	1.68	38	2	<1	2248	1.04	<10	0.10	1477	65	0.01	1	90	5476	5	<20	86	<0.01	<10	6	<10	1	6949

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish



ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/n5651
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5652

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

12-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 070
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05238	0.83	0.024
2	X05239	0.95	0.028
3	X05240	1.14	0.033
4	X05241	0.71	0.021
5	X05242	0.35	0.010
6	X05243	1.26	0.037
7	X05244	1.21	0.035
8	X05245	0.97	0.028
9	X05246	0.92	0.027
10	X05247	1.06	0.031
11	X05248	4.20	0.122
12	X05249	0.66	0.019
13	X05250	<0.03	<0.001
14	X05251	0.85	0.025
15	X05252	0.98	0.029
16	X05253	0.65	0.019
17	X05254	0.91	0.027
18	X05255	0.69	0.020
19	X05256	0.27	0.008
20	X05257	0.68	0.020
21	X05258	0.81	0.024
22	X05259	1.02	0.030
23	X05260	0.28	0.008
24	X05261	0.93	0.027
25	X05262	0.62	0.018
26	X05263	0.74	0.022

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7 - 5652

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	X05264	1.38	0.040
28	X05265	0.46	0.013
29	X05266	0.62	0.018
30	X05267	0.55	0.016
31	X05268	0.43	0.013
32	X05269	0.41	0.012
33	X05270	0.07	0.002
34	X05271	0.74	0.022
35	X05272	0.55	0.016
QC DATA:			
Repeat:			
1	X05238	0.93	0.027
10	X05247	1.02	0.030
11	X05248	4.23	0.123
19	X05256	0.29	0.008
27	X05264	1.43	0.042
Resplits:			
1	X05238	0.86	0.025
Standard:			
OXI54		1.82	0.053

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
XLS/07

11-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5652

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1


No. of samples received: 35
Sample Type: Core
Project: KSM
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05238	0.8	0.46	<5	45	<5	0.30	3	12	187	1329	5.47	<10	0.08	191	87	0.02	7	1160	48	<5	<20	28	0.01	<10	9	<10	<1	149
2	X05239	0.8	0.39	<5	45	<5	0.26	2	14	151	1528	4.91	<10	0.03	144	100	0.02	6	1010	30	<5	<20	24	0.01	<10	8	<10	<1	77
3	X05240	0.9	0.42	<5	55	<5	0.18	1	15	171	1678	5.34	<10	0.04	110	91	0.02	7	630	28	<5	<20	31	0.01	<10	9	<10	<1	47
4	X05241	1.3	0.37	5	65	<5	0.13	3	18	141	1452	7.60	<10	0.03	81	176	0.01	9	440	102	10	<20	30	0.02	<10	8	<10	<1	60
5	X05242	0.7	0.42	<5	35	<5	0.28	1	11	157	968	4.35	<10	0.06	81	59	0.02	6	1190	74	<5	<20	26	<0.01	<10	9	<10	<1	48
6	X05243	1.0	0.38	20	45	<5	0.31	1	11	163	1273	5.02	<10	0.05	163	78	0.02	7	1080	32	10	<20	41	0.01	<10	9	<10	<1	37
7	X05244	1.3	0.32	<5	60	<5	0.31	2	13	171	1322	5.51	<10	<0.01	74	55	0.02	8	1320	30	<5	<20	44	0.01	<10	8	<10	<1	49
8	X05245	0.8	0.35	<5	55	<5	0.30	1	13	157	1126	4.36	<10	0.03	83	53	0.02	5	1260	30	<5	<20	34	0.01	<10	7	<10	<1	60
9	X05246	2.4	0.46	<5	60	<5	0.40	2	14	142	1770	6.77	<10	0.07	157	53	0.02	9	1740	38	<5	<20	27	0.02	<10	10	<10	<1	91
10	X05247	2.0	0.47	<5	55	<5	0.39	2	12	150	1723	6.08	<10	0.08	159	68	0.02	7	1530	36	<5	<20	29	0.01	<10	10	<10	<1	72
11	X05248	2.6	0.48	<5	65	<5	0.30	3	13	166	1495	6.09	<10	0.10	135	61	0.02	13	1190	42	<5	<20	36	0.01	<10	10	<10	<1	115
12	X05249	2.3	0.46	<5	55	<5	0.26	2	15	158	1606	5.63	<10	0.11	139	38	0.02	13	990	48	5	<20	26	0.02	<10	8	<10	<1	114
13	X05250	<0.2	1.09	<5	270	20	0.60	<1	7	105	8	2.21	10	0.61	527	2	0.12	5	920	24	5	<20	86	0.13	<10	46	<10	3	42
14	X05251	2.1	0.52	5	65	<5	0.35	2	18	150	1555	6.58	<10	0.14	151	44	0.02	10	1400	58	<5	<20	40	0.02	<10	10	<10	<1	115
15	X05252	1.9	0.45	<5	55	<5	0.36	3	17	146	1639	6.16	<10	0.09	116	52	0.02	15	1480	52	<5	<20	27	0.02	<10	9	<10	<1	276
16	X05253	1.7	0.57	<5	55	<5	0.93	2	13	138	2199	4.61	<10	0.15	141	119	0.02	7	4330	40	<5	<20	33	0.01	<10	9	<10	3	145
17	X05254	1.9	0.47	<5	55	<5	0.37	2	12	123	1893	5.59	<10	0.11	114	83	0.02	8	1560	46	<5	<20	22	0.01	<10	9	<10	<1	93
18	X05255	1.4	0.49	<5	55	<5	0.50	2	16	168	1870	5.14	<10	0.06	105	77	0.02	7	2160	32	<5	<20	40	0.01	<10	10	<10	1	89
19	X05256	0.3	1.09	40	50	20	0.35	1	40	60	83	4.35	<10	0.37	236	7	0.02	3	1640	34	<5	<20	22	0.01	<10	42	<10	3	129
20	X05257	0.9	0.77	<5	65	<5	0.35	1	17	142	1185	6.50	<10	0.24	183	37	0.02	7	1510	26	<5	<20	32	0.02	<10	17	<10	<1	79
21	X05258	1.5	0.55	<5	60	<5	0.37	2	16	148	1820	5.57	<10	0.16	134	66	0.02	8	1560	60	<5	<20	36	0.02	<10	10	<10	<1	82
22	X05259	1.7	0.47	<5	35	<5	0.25	2	11	118	2935	4.42	<10	0.14	96	82	0.02	16	910	32	5	<20	26	<0.01	<10	8	<10	<1	54
23	X05260	3.2	1.23	25	45	<5	0.98	3	21	59	2630	3.64	20	0.64	191	205	0.04	8	460	72	15	<20	53	0.05	<10	48	<10	3	271
24	X05261	1.5	0.37	<5	50	<5	0.27	2	15	115	1763	6.24	<10	0.04	64	46	0.02	17	1040	32	<5	<20	28	0.01	<10	6	<10	<1	39
25	X05262	2.2	0.50	20	50	<5	0.24	2	18	134	1566	5.56	<10	0.14	115	54	0.02	18	850	54	<5	<20	48	0.01	<10	9	<10	<1	146

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05263	1.8	0.46	<5	45	<5	0.30	2	12	120	1497	4.29	<10	0.13	113	85	0.02	16	1140	62	<5	<20	42	0.01	<10	8	<10	<1	229
27	X05264	2.0	0.52	<5	50	<5	0.34	2	17	113	1671	5.27	<10	0.17	122	154	0.02	11	1430	34	<5	<20	32	0.01	<10	8	<10	<1	149
28	X05265	1.4	0.56	<5	50	<5	0.49	2	15	119	1441	5.77	<10	0.17	122	83	0.02	7	2160	36	<5	<20	36	0.01	<10	9	<10	<1	91
29	X05266	1.8	0.63	<5	55	<5	0.65	2	17	114	1660	6.20	<10	0.12	117	175	0.03	5	2960	54	<5	<20	40	0.02	<10	11	<10	1	104
30	X05267	1.5	0.83	<5	60	<5	0.47	1	15	112	1346	6.11	<10	0.33	207	101	0.02	6	2120	38	<5	<20	30	0.02	<10	12	<10	<1	141
31	X05268	1.6	0.62	<5	50	<5	0.58	5	15	128	2105	6.03	<10	0.17	106	113	0.02	6	2610	46	<5	<20	21	0.01	<10	10	<10	<1	267
32	X05269	1.3	0.50	<5	50	<5	0.43	2	14	119	1135	6.30	<10	0.11	95	80	0.02	5	1890	80	<5	<20	29	0.01	<10	9	<10	<1	110
33	X05270	0.2	5.94	45	70	25	0.19	1	46	171	108	6.87	<10	4.62	1222	17	0.01	110	850	132	35	<20	21	0.03	<10	151	<10	2	176
34	X05271	1.6	1.43	<5	55	<5	0.35	2	20	84	1527	6.46	<10	0.74	328	93	0.02	9	1490	128	5	<20	21	0.02	<10	22	<10	<1	305
35	X05272	1.3	1.78	<5	60	<5	0.35	2	15	96	1279	5.65	<10	0.88	419	61	0.02	8	1580	64	5	<20	12	0.02	<10	27	<10	<1	222
QC DATA:																													
Repeat:																													
1	X05238	0.9	0.42	<5	45	<5	0.29	3	12	172	1303	5.33	<10	0.07	181	78	0.02	6	1150	44	<5	<20	25	0.01	<10	8	<10	<1	137
10	X05247	2.1	0.42	<5	50	<5	0.39	2	13	143	1743	6.12	<10	0.08	160	63	0.02	9	1570	38	<5	<20	26	0.01	<10	9	<10	<1	72
19	X05256	0.4	1.13	30	50	25	0.36	2	41	59	81	4.52	<10	0.40	249	8	0.02	4	1700	34	5	<20	21	0.01	<10	43	<10	3	134
Resplit:																													
1	X05238	0.8	0.47	<5	50	<5	0.29	3	12	172	1360	5.57	<10	0.07	182	63	0.02	7	1130	40	<5	<20	26	0.01	<10	8	<10	<1	136
Standard:																													
PB113A		10.9	0.26	45	60	<5	1.65	37	2	6	2280	1.07	<10	0.10	1416	70	0.02	2	70	5426	20	<20	99	0.02	<10	7	<10	<1	6988

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish



ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5652S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5653

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

20-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07157
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	X09762	2.68	0.078	59.8	1.74
2	X09763	1.01	0.029		
3	X09764	0.70	0.020		
4	X09765	1.13	0.033		
5	X09766	1.52	0.044		
6	X09767	0.91	0.027		
7	X09768	1.49	0.043		
8	X09769	0.78	<0.001		
9	X09770	0.70	0.020		
10	X09771	1.70	0.050		
11	X09772	0.92	0.027		
12	X09773	0.29	0.008		
13	X09774	0.89	0.026		
14	X09775	0.66	0.019		
15	X09776	<0.03	<0.001		
16	X09777	0.55	0.016		
17	X09778	1.15	0.034		
18	X09779	1.15	0.034		
19	X09780	0.83	0.024		
20	X09781	0.94	0.027		
21	X09782	0.83	0.024		
22	X09783	1.77	0.052		
23	X09784	0.44	0.013		
24	X09785	1.23	0.036		
25	X09786	1.65	0.048		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5653

20-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
26	X09787	1.35	0.039		
27	X09788	0.79	0.023		
28	X09789	1.46	0.043		
29	X09790	1.71	0.050		
30	X09791	1.03	0.030		
31	X09792	0.78	0.023		
32	X09793	2.03	0.059		
33	X09794	0.85	0.025		
34	X09795	0.67	0.020		
35	X09796	0.62	0.018		
QC DATA:					
Repeat:					
1	X09762	2.70	0.079		
7	X09768	1.62	0.047		
8	X09769	0.73	0.021		
10	X09771	1.55	0.045		
19	X09780	0.84	0.024		
22	X09783	1.69	0.049		
25	X09786	1.49	0.043		
32	X09793	1.89	0.055		
Resplits:					
1	X09762	2.80	0.082		
Standard:					
OXK48		3.53	0.103		
Pb113				22.5	0.656

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
XLS/07

20-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5653

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07157
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09762	>30	0.19	320	45	<5	0.20	26	7	104	1961	4.30	<10	0.02	207	14	<0.01	4	480	230	145	<20	21	<0.01	<10	5	<10	<1	546
2	X09763	18.2	0.23	130	50	<5	0.22	10	12	100	1642	5.58	10	0.02	121	23	<0.01	6	730	94	60	<20	16	0.02	<10	5	<10	<1	109
3	X09764	14.1	0.22	120	40	<5	0.21	11	10	113	1991	4.10	<10	0.03	117	16	<0.01	5	680	60	65	<20	16	<0.01	<10	4	<10	1	227
4	X09765	12.1	0.22	100	50	<5	0.25	8	10	89	1618	4.22	<10	0.02	114	18	<0.01	4	850	36	60	<20	30	0.02	<10	3	<10	2	104
5	X09766	6.2	0.23	50	40	<5	0.28	4	9	85	1565	4.14	<10	0.04	157	15	<0.01	1	900	50	5	<20	15	0.02	<10	3	<10	2	92
6	X09767	4.7	1.23	<5	50	<5	0.19	2	12	119	2453	5.20	<10	0.74	293	13	<0.01	5	810	26	5	<20	12	0.02	<10	14	<10	<1	89
7	X09768	4.2	2.21	<5	70	<5	0.90	2	12	71	3522	5.85	10	1.46	847	16	<0.01	7	1080	44	30	<20	42	0.02	<10	29	<10	2	149
8	X09769	2.1	1.21	<5	50	<5	1.91	1	9	97	2597	3.89	<10	0.86	1055	13	<0.01	5	890	28	10	<20	82	0.02	<10	13	<10	1	84
9	X09770	1.9	1.46	<5	55	<5	1.36	2	11	96	2265	4.42	<10	0.91	915	16	<0.01	5	930	34	25	<20	61	0.02	<10	16	<10	2	94
10	X09771	2.8	0.29	10	40	<5	0.28	2	10	107	2246	4.47	<10	0.07	122	12	<0.01	4	850	32	<5	<20	8	0.01	<10	4	<10	<1	40
11	X09772	1.5	1.20	15	45	<5	1.27	3	11	68	1775	4.37	10	1.07	1442	25	<0.01	8	1210	28	30	<20	32	0.05	<10	14	<10	4	118
12	X09773	3.0	1.19	30	45	<5	0.98	3	21	56	2741	3.51	20	0.67	196	189	0.03	9	430	62	10	<20	49	0.08	<10	46	<10	8	268
13	X09774	2.3	1.47	<5	60	<5	1.45	2	10	94	3228	4.13	10	1.17	1245	14	<0.01	4	1000	30	10	<20	52	0.02	<10	16	<10	3	113
14	X09775	1.2	2.27	<5	95	<5	2.14	3	10	73	2388	4.69	10	1.64	1228	20	0.02	7	1150	40	40	<20	111	0.09	<10	46	<10	5	108
15	X09776	<0.2	1.08	<5	245	10	0.57	<1	6	101	9	2.14	10	0.62	504	<1	0.11	4	950	18	5	<20	85	0.14	<10	45	<10	7	39
16	X09777	1.4	1.22	<5	50	<5	2.24	2	12	86	2638	4.59	10	0.80	868	17	0.02	5	950	36	15	<20	129	0.02	<10	28	<10	3	68
17	X09778	2.0	1.11	<5	60	<5	1.08	2	12	90	3250	4.71	10	0.72	726	18	<0.01	6	880	30	20	<20	56	0.02	<10	14	<10	2	78
18	X09779	2.5	0.71	<5	35	<5	0.81	6	10	82	2820	3.95	10	0.44	510	19	<0.01	5	870	40	15	<20	24	<0.01	<10	8	<10	1	123
19	X09780	1.4	0.68	<5	50	<5	1.31	3	10	85	1518	4.23	10	0.43	789	19	<0.01	5	910	42	15	<20	60	0.03	<10	9	<10	3	80
20	X09781	1.7	0.49	<5	40	<5	1.57	2	9	90	2107	3.45	<10	0.30	679	19	<0.01	5	880	40	<5	<20	69	0.02	<10	7	<10	2	57
21	X09782	0.6	1.03	<5	35	<5	3.84	2	10	66	1238	3.33	<10	0.84	1327	19	0.02	4	990	24	15	<20	1125	0.04	<10	21	<10	2	102
22	X09783	2.5	0.59	5	45	<5	1.07	6	12	92	2878	3.92	<10	0.35	461	17	<0.01	7	910	28	15	<20	103	<0.01	<10	7	<10	3	158
23	X09784	0.9	1.52	<5	115	<5	2.84	2	8	64	1375	3.31	10	1.03	1225	20	0.03	4	1020	24	20	<20	1711	0.04	<10	33	<10	4	171
24	X09785	3.3	0.31	<5	45	<5	0.62	5	12	107	3515	4.32	<10	0.08	387	21	<0.01	6	690	78	5	<20	31	<0.01	<10	5	<10	2	95
25	X09786	13.8	0.47	120	45	<5	0.48	9	9	101	2074	4.01	<10	0.27	497	13	<0.01	5	720	66	85	<20	27	0.01	<10	7	<10	1	185

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09787	5.7	0.24	50	40	<5	0.26	5	9	102	1418	3.85	<10	0.01	134	17	<0.01	4	890	66	10	<20	11	0.01	<10	6	<10	2	155
27	X09788	3.4	0.35	25	40	<5	0.44	5	11	66	1508	4.38	10	0.13	307	17	<0.01	4	1180	22	<5	<20	14	0.02	<10	5	<10	2	132
28	X09789	3.5	0.21	30	45	<5	0.63	5	12	87	2512	4.91	<10	<0.01	318	13	<0.01	5	850	68	<5	<20	27	0.01	<10	4	<10	2	85
29	X09790	3.3	0.22	20	55	<5	0.31	5	12	93	1695	5.36	10	<0.01	143	13	<0.01	6	850	54	<5	<20	21	0.02	<10	4	<10	1	95
30	X09791	2.8	0.85	10	55	<5	0.25	3	12	75	1889	4.27	<10	0.40	217	16	<0.01	4	1100	38	10	<20	28	0.02	<10	8	<10	3	129
31	X09792	2.8	0.69	<5	45	<5	0.28	2	11	74	2085	4.09	<10	0.28	171	18	<0.01	3	1260	34	10	<20	9	0.01	<10	9	<10	3	72
32	X09793	3.3	0.23	15	45	<5	0.26	3	10	92	1615	4.38	<10	<0.01	36	17	<0.01	4	1120	82	<5	<20	13	0.02	<10	5	<10	2	116
33	X09794	2.5	1.05	<5	65	<5	0.39	2	11	76	2714	4.15	<10	0.59	290	25	<0.01	6	1350	52	25	<20	34	<0.01	<10	11	<10	4	170
34	X09795	1.7	1.47	10	70	<5	2.10	2	10	82	1948	3.65	<10	0.93	1008	19	0.01	4	1240	56	20	<20	171	0.03	<10	19	<10	4	169
35	X09796	1.0	1.30	<5	45	<5	2.51	2	10	49	1687	3.41	<10	1.05	1145	19	0.02	4	1260	34	20	<20	799	0.03	<10	25	<10	4	170
QC DATA:																													
Repeat:																													
1	X09762	>30	0.20	325	40	<5	0.20	26	7	104	1972	4.33	<10	0.02	208	15	<0.01	4	480	228	140	<20	16	0.01	<10	6	<10	<1	540
10	X09771	2.8	0.31	<5	55	<5	0.29	2	11	113	2352	4.52	<10	0.08	125	13	<0.01	5	840	36	<5	<20	10	0.01	<10	4	<10	2	40
19	X09780	1.5	0.70	<5	45	<5	1.35	3	10	90	1545	4.37	10	0.44	812	20	<0.01	6	940	42	15	<20	52	0.02	<10	10	<10	2	85
Resplit:																													
1	X09762	>30	0.21	315	40	<5	0.21	28	8	106	2005	4.49	<10	0.01	199	12	<0.01	6	540	248	165	<20	19	0.02	<10	5	<10	<1	573
Standard:																													
Pb113a		11.6	0.27	25	50	<5	1.68	39	3	5	2239	1.06	<10	0.11	1465	64	0.02	3	60	5542	15	<20	85	0.01	<10	7	<10	<1	6977

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
df/5653
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5654

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

12-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05273	0.59	0.017
2	X05274	0.72	0.021
3	X05275	0.68	0.020
4	X05276	0.53	0.015
5	X05277	0.81	0.024
6	X05278	0.80	0.023
7	X05279	1.09	0.032
8	X05280	0.72	0.021
9	X05281	0.63	0.018
10	X05282	0.85	0.025
11	X05283	0.45	0.013
12	X05284	0.66	0.019
13	X05285	0.81	0.024
14	X05286	1.12	0.033
15	X05287	0.70	0.020
16	X05288	0.60	0.017
17	X05289	0.78	0.023
18	X05290	0.70	0.020
19	X05291	0.74	0.022
20	X05292	0.61	0.018
21	X05293	0.47	0.014
22	X05294	0.46	0.013
23	X05295	0.72	0.021
24	X05296	0.64	0.019
25	X05297	0.49	0.014
26	X05298	<0.03	<0.001

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AWS - 5654

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	X05299	1.02	0.030
28	X05300	0.81	0.024
29	X05301	0.73	0.021
30	X05302	0.58	0.017
31	X05303	0.54	0.016
32	X05304	0.69	0.020
33	X05305	0.37	0.011
34	X05306	0.26	0.008
35	X05307	0.48	0.014

QC DATA:

Repeat:

1	X05273	0.64	0.019
7	X05279	1.16	0.034
10	X05282	0.84	0.024
14	X05286	1.24	0.036
19	X05291	0.74	0.022
22	X05294	0.47	0.014
35	X05307	0.53	0.015

Resplits:

1	X05273	0.61	0.018

Standard:

OXI54		1.87	0.055

AU: 30g FA/AA-Finish

JJ/jl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

11-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5654

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05273	1.6	1.56	<5	60	<5	0.33	1	12	86	1204	5.34	<10	0.76	423	73	0.02	5	1400	94	10	<20	19	0.02	<10	25	<10	<1	111
2	X05274	1.7	1.46	<5	60	<5	0.35	2	14	91	1401	5.29	10	0.68	438	96	0.02	5	1440	80	5	<20	22	0.02	<10	23	<10	<1	122
3	X05275	1.8	1.04	<5	50	<5	0.47	2	17	94	1482	5.85	<10	0.39	325	90	0.02	7	1930	62	5	<20	13	0.01	<10	16	<10	<1	150
4	X05276	1.3	1.18	<5	50	<5	0.45	2	14	78	1168	5.56	<10	0.53	366	90	0.02	5	1980	46	<5	<20	10	0.01	<10	18	<10	<1	110
5	X05277	1.6	0.97	<5	50	<5	0.31	1	18	114	1613	5.45	<10	0.45	302	79	0.02	13	1150	52	<5	<20	14	0.01	<10	13	<10	<1	104
6	X05278	2.1	0.69	<5	55	<5	0.42	2	16	84	1458	4.39	<10	0.27	193	97	0.02	6	1700	58	<5	<20	24	0.01	<10	10	<10	<1	88
7	X05279	1.9	0.70	<5	45	<5	0.40	2	16	95	1610	4.88	10	0.29	194	56	0.01	6	1540	58	<5	<20	13	0.01	<10	10	<10	<1	92
8	X05280	3.6	0.76	<5	50	<5	0.40	4	17	91	1656	4.96	<10	0.36	202	62	0.01	8	1520	92	10	<20	19	<0.01	<10	11	<10	<1	121
9	X05281	2.1	0.92	<5	50	<5	0.35	2	16	83	1367	5.40	10	0.48	239	77	0.01	6	1380	46	5	<20	19	0.01	<10	13	<10	<1	98
10	X05282	2.8	0.81	<5	50	<5	0.35	2	16	105	1675	5.55	<10	0.37	210	145	0.02	7	1340	54	<5	<20	25	0.01	<10	12	<10	<1	90
11	X05283	2.3	0.72	<5	45	<5	0.40	1	14	123	1328	4.69	<10	0.28	158	100	0.02	6	1470	84	<5	<20	19	0.01	<10	12	<10	<1	74
12	X05284	1.8	0.86	<5	50	<5	0.33	1	16	97	1370	4.90	<10	0.37	190	194	0.01	4	1320	74	<5	<20	14	0.01	<10	13	<10	<1	112
13	X05285	1.6	1.46	<5	70	<5	0.34	2	19	75	1389	6.59	10	0.72	340	99	0.02	4	1370	68	<5	<20	20	0.02	<10	22	<10	<1	169
14	X05286	1.9	2.02	<5	65	<5	0.36	1	17	78	1654	5.79	<10	1.03	476	124	0.01	4	1400	66	<5	<20	21	0.02	<10	31	<10	<1	155
15	X05287	1.1	2.73	<5	75	<5	0.40	1	13	60	1234	6.03	<10	1.46	664	125	0.01	3	1430	82	10	<20	23	0.02	<10	45	<10	<1	156
16	X05288	1.4	1.42	<5	50	<5	0.40	2	19	89	1312	5.13	<10	0.75	343	89	0.02	4	1300	78	<5	<20	21	0.01	<10	24	<10	<1	131
17	X05289	1.5	1.66	<5	55	<5	0.40	1	18	89	1362	6.22	10	0.83	378	79	0.02	5	1490	92	<5	<20	20	0.02	<10	24	<10	<1	188
18	X05290	1.2	2.23	<5	65	<5	0.44	2	13	66	1175	5.60	<10	1.14	574	130	0.02	5	1400	70	10	<20	27	0.02	<10	35	<10	<1	120
19	X05291	1.1	2.17	<5	70	<5	0.44	2	15	71	1238	5.71	<10	1.11	563	142	0.02	5	1400	72	10	<20	25	0.02	<10	34	<10	<1	118
20	X05292	1.1	2.28	<5	70	<5	0.41	2	13	74	1110	5.60	<10	1.37	612	81	0.02	9	1470	68	5	<20	22	0.02	<10	39	<10	<1	100
21	X05293	1.0	2.64	<5	65	<5	0.22	2	15	74	974	6.04	10	1.73	700	87	0.02	20	880	68	15	<20	5	0.02	<10	36	<10	<1	124
22	X05294	0.8	2.08	<5	60	<5	0.24	1	12	71	649	4.98	<10	1.40	575	104	0.02	15	890	78	10	<20	10	0.02	<10	30	<10	<1	103
23	X05295	1.4	2.85	<5	65	<5	0.29	1	20	90	1451	5.70	<10	2.00	828	109	0.02	17	980	90	10	<20	13	0.02	<10	43	<10	<1	141
24	X05296	1.8	1.93	<5	65	<5	0.23	2	19	74	1292	5.80	<10	1.23	569	85	0.02	14	910	88	<5	<20	15	0.02	<10	28	<10	<1	124
25	X05297	1.3	1.57	<5	45	<5	0.31	3	15	67	1002	4.66	<10	1.05	448	205	0.02	18	1150	64	10	<20	8	0.02	<10	24	<10	<1	97

ECO TECH LABORATORY LTD. | ICP CERTIFICATE OF ANALYSIS AS 2007-5654 | Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05298	<0.2	1.06	<5	280	20	0.57	<1	7	113	7	2.35	10	0.65	554	4	0.10	6	950	22	10	<20	75	0.13	<10	49	<10	2	45
27	X05299	3.7	1.11	45	70	<5	0.73	4	17	57	3271	3.85	30	0.52	268	209	0.03	12	390	138	35	<20	29	0.03	<10	43	<10	3	161
28	X05300	1.6	1.64	<5	60	<5	0.24	2	13	104	1112	5.48	<10	1.19	530	118	0.02	15	680	96	15	<20	9	0.02	<10	22	<10	<1	97
29	X05301	1.2	1.02	<5	55	<5	0.28	3	16	92	1273	5.27	<10	0.62	372	63	0.02	19	760	60	20	<20	19	0.01	<10	13	<10	<1	94
30	X05302	1.0	1.63	<5	50	<5	0.35	1	15	84	1243	4.81	<10	1.23	652	178	0.02	16	750	56	10	<20	25	0.02	<10	29	<10	<1	115
31	X05303	1.3	1.51	<5	50	<5	0.40	1	15	68	1142	4.13	<10	1.13	636	100	0.02	18	1110	46	10	<20	22	0.01	<10	26	<10	<1	70
32	X05304	1.2	0.96	<5	55	<5	0.21	2	15	106	1170	4.46	<10	0.61	399	82	0.02	15	380	46	10	<20	15	0.01	<10	14	<10	<1	68
33	X05305	1.2	0.55	30	40	<5	0.15	3	9	125	1065	3.38	<10	0.25	155	86	0.02	9	400	58	10	<20	18	<0.01	<10	5	<10	<1	50
34	X05306	1.3	0.60	75	40	<5	0.13	3	11	105	1246	3.43	<10	0.25	95	58	0.02	10	350	70	20	<20	25	<0.01	<10	7	<10	<1	45
35	X05307	1.4	0.60	60	45	<5	0.12	3	12	108	1433	4.07	<10	0.23	77	106	0.02	10	330	74	10	<20	22	<0.01	<10	8	<10	<1	40
QC DATA:																													
Repeat:																													
1	X05273	1.8	1.60	<5	50	<5	0.33	2	13	84	1251	5.52	10	0.80	442	68	0.02	6	1400	90	10	<20	17	0.01	<10	25	<10	<1	113
10	X05282	2.7	0.83	<5	50	<5	0.35	2	17	104	1690	5.64	10	0.40	220	137	0.01	8	1330	54	5	<20	28	0.01	<10	13	<10	<1	93
19	X05291	1.0	2.10	<5	65	<5	0.44	1	14	68	1238	5.59	10	1.09	549	138	0.01	4	1390	68	5	<20	19	0.02	<10	32	<10	<1	114
Resplit:																													
1	X05273	1.7	1.60	<5	55	<5	0.37	2	12	82	1187	5.64	10	0.87	465	67	0.02	6	1430	88	10	<20	17	0.02	<10	27	<10	<1	116
Standard:																													
PB113A		11.7	0.23	50	60	<5	1.66	38	2	6	2298	1.08	<10	0.11	1391	65	0.02	2	60	5444	15	<20	84	0.01	<10	7	<10	<1	6995

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5652S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5655

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

20-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07159
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05308	0.49	0.014
2	X05309	0.46	0.013
3	X05310	0.45	0.013
4	X05311	0.51	0.015
5	X05312	0.46	0.013
6	X05313	0.37	0.011
7	X05314	0.51	0.015
8	X05315	0.46	0.013
9	X05316	0.37	0.011
10	X05317	0.28	0.008
11	X05318	0.41	0.012
12	X05319	0.57	0.017
13	X05320	0.13	0.004
14	X05321	0.18	0.005
15	X05322	0.44	0.013
16	X05323	0.17	0.005
17	X05324	0.16	0.005
18	X05325	0.18	0.005
19	X05326	0.16	0.005
20	X05327	0.39	0.011
21	X05328	0.30	0.009
22	X05329	0.18	0.005
23	X05330	0.37	0.011
24	X05331	0.24	0.007
25	X05332	0.14	0.004

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5655 20-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X05333	0.31	0.009
27	X05334	0.32	0.009
28	X05335	0.07	0.002
29	X05336	0.39	0.011
30	X05337	0.30	0.009
31	X05338	0.23	0.007
32	X05339	0.30	0.009
33	X05340	<0.03	<0.001
34	X05341	0.89	0.026
35	X05342	1.53	0.045
QC DATA:			
Repeat:			
1	X05308	0.41	0.012
10	X05317	0.30	0.009
19	X05326	0.16	0.005
Resplits:			
1	X05308	0.44	0.013
35	X05342	1.60	0.047
Standard:			
OXK48		3.52	0.103

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
XLS/07

21-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5655

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07159
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05308	0.8	0.64	<5	25	<5	0.14	<1	10	103	884	3.44	<10	0.27	108	67	0.02	12	520	38	<5	<20	7	0.03	<10	9	<10	<1	42
2	X05309	1.3	0.74	<5	30	<5	0.21	2	18	114	1179	5.18	<10	0.33	164	117	0.03	26	780	52	<5	<20	18	0.03	<10	16	<10	<1	57
3	X05310	1.1	1.51	5	30	<5	0.25	2	16	92	937	4.45	<10	0.89	350	83	0.04	21	1040	34	15	<20	11	0.03	<10	35	<10	<1	110
4	X05311	1.3	0.93	<5	30	<5	0.21	2	19	124	1169	4.50	<10	0.47	227	141	0.04	22	860	32	10	<20	16	0.03	<10	21	<10	<1	84
5	X05312	1.6	0.74	5	30	<5	0.18	2	14	108	999	3.57	<10	0.37	185	100	0.04	17	720	38	<5	<20	20	0.03	<10	16	<10	<1	82
6	X05313	1.1	0.90	10	30	<5	0.21	<1	15	98	995	4.19	<10	0.46	193	61	0.04	21	880	34	<5	<20	22	0.03	<10	23	<10	<1	83
7	X05314	1.4	0.90	10	25	<5	0.19	<1	14	98	1334	3.74	<10	0.50	204	241	0.04	19	770	32	<5	<20	14	0.03	<10	21	<10	<1	88
8	X05315	1.8	0.82	105	30	<5	0.35	2	17	103	941	5.21	<10	0.39	208	65	0.03	20	1510	30	<5	<20	13	0.04	<10	16	<10	<1	89
9	X05316	2.1	0.84	<5	25	<5	0.32	4	20	113	1115	6.06	<10	0.40	241	73	0.02	11	1430	50	20	<20	11	0.03	<10	15	<10	<1	86
10	X05317	1.4	1.53	<5	45	<5	0.33	2	14	95	711	5.37	<10	1.03	531	260	0.02	7	1480	70	15	<20	17	0.04	<10	33	<10	<1	125
11	X05318	1.9	1.47	<5	35	<5	0.37	3	15	89	966	4.86	<10	1.03	518	117	0.02	6	1620	76	20	<20	27	0.04	<10	34	<10	2	149
12	X05319	1.6	1.25	<5	35	<5	0.36	33	17	85	1092	5.65	<10	0.83	433	96	0.02	8	1640	124	<5	<20	13	0.03	<10	24	<10	<1	235
13	X05320	1.5	2.46	80	35	<5	0.26	<1	14	132	267	3.89	<10	1.89	700	27	0.02	20	1020	618	<5	<20	6	0.04	<10	61	<10	1	154
14	X05321	2.1	4.94	135	45	<5	0.29	6	31	71	604	7.69	<10	4.36	1564	49	0.02	48	1310	184	50	<20	16	0.07	<10	118	<10	<1	344
15	X05322	2.8	4.69	165	40	<5	0.79	12	33	77	632	8.04	<10	4.67	1906	84	0.01	40	3620	420	85	<20	11	0.06	<10	142	<10	<1	452
16	X05323	1.1	3.50	40	35	<5	0.45	3	15	67	526	4.63	<10	2.90	1100	58	0.02	25	2040	124	35	<20	24	0.04	<10	86	<10	4	257
17	X05324	0.3	2.82	10	45	<5	0.34	1	13	69	238	3.65	<10	2.32	900	60	0.03	21	1540	52	25	<20	26	0.04	<10	61	<10	4	145
18	X05325	0.5	2.33	10	35	<5	0.23	1	13	65	306	3.18	<10	1.73	612	173	0.02	17	980	72	25	<20	15	0.03	<10	38	<10	2	88
19	X05326	0.4	2.57	10	40	<5	0.30	<1	12	70	313	3.09	<10	2.05	739	98	0.02	18	1290	68	10	<20	23	0.04	<10	47	<10	4	105
20	X05327	0.7	3.08	<5	35	<5	0.28	3	47	90	780	6.58	<10	2.55	926	64	0.03	30	1060	122	40	<20	12	0.05	<10	61	<10	<1	106
21	X05328	0.6	2.39	<5	35	<5	0.22	2	26	78	609	5.07	<10	1.90	640	29	0.02	22	930	60	25	<20	13	0.04	<10	44	<10	<1	98
22	X05329	0.2	2.83	<5	40	<5	0.23	2	17	73	284	3.71	<10	2.30	714	50	0.03	22	1040	58	40	<20	26	0.03	<10	52	<10	3	90
23	X05330	0.5	2.47	<5	35	<5	0.23	2	14	81	342	4.63	<10	2.00	654	60	0.03	24	990	36	30	<20	16	0.04	<10	45	<10	1	85
24	X05331	0.4	2.04	<5	35	<5	0.27	1	15	67	279	4.12	<10	1.50	556	26	0.04	22	1140	26	15	<20	15	0.03	<10	34	<10	2	61
25	X05332	0.3	2.21	<5	25	<5	0.32	2	14	65	263	4.74	<10	1.68	622	64	0.04	24	1430	28	30	<20	10	0.03	<10	43	<10	1	63

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05333	0.4	1.72	<5	35	<5	0.20	1	14	93	317	4.24	<10	1.21	455	68	0.03	19	870	22	10	<20	12	0.03	<10	27	<10	<1	53
27	X05334	0.3	1.97	<5	35	<5	0.19	2	13	84	331	4.56	<10	1.41	531	20	0.03	17	810	22	10	<20	12	0.03	<10	30	<10	<1	62
28	X05335	0.2	0.94	75	140	<5	0.20	<1	73	212	454	>10	<10	0.21	509	126	0.06	448	160	124	35	<20	13	0.03	<10	26	<10	<1	394
29	X05336	0.4	1.04	<5	35	<5	0.13	1	11	84	433	4.04	<10	0.67	250	26	0.03	15	540	28	10	<20	16	0.03	<10	10	<10	<1	30
30	X05337	0.5	1.05	<5	40	<5	0.16	<1	12	117	294	4.59	<10	0.67	242	43	0.02	14	680	28	5	<20	19	0.04	<10	11	<10	<1	34
31	X05338	0.4	1.35	<5	30	<5	0.19	2	12	93	370	5.08	<10	0.96	295	18	0.02	15	560	24	10	<20	10	0.04	<10	11	<10	<1	44
32	X05339	0.5	0.97	<5	30	<5	0.30	3	17	68	462	6.12	<10	0.60	193	25	0.02	20	1060	24	25	<20	5	0.05	<10	10	<10	<1	36
33	X05340	<0.2	1.06	<5	250	25	0.61	<1	7	113	5	2.21	<10	0.60	532	<1	0.10	2	920	18	<5	<20	94	0.10	<10	47	<10	<1	45
34	X05341	1.8	1.42	<5	45	<5	0.41	<1	23	85	1043	>10	<10	0.80	304	43	0.02	14	1220	26	<5	<20	17	0.09	<10	25	<10	<1	73
35	X05342	2.8	3.98	15	80	<5	0.53	10	47	73	744	>10	<10	2.47	892	46	0.01	40	2350	52	80	<20	19	0.11	<10	121	<10	<1	189
QC DATA:																													
Repeat:																													
1	X05308	0.9	0.77	<5	20	<5	0.15	<1	11	114	935	3.57	<10	0.30	117	75	0.03	12	560	40	<5	<20	5	0.03	<10	11	<10	<1	45
10	X05317	1.4	1.56	<5	35	<5	0.33	2	14	99	734	5.37	<10	1.06	539	265	0.02	7	1450	70	15	<20	20	0.04	<10	33	<10	1	124
19	X05326	0.3	2.71	10	40	<5	0.30	<1	12	73	318	3.14	<10	2.23	768	96	0.03	17	1290	68	5	<20	20	0.04	<10	52	<10	4	107
Resplit:																													
1	X05308	0.8	0.83	<5	30	<5	0.15	2	11	108	913	3.73	<10	0.30	107	71	0.03	15	520	40	5	<20	8	0.03	<10	12	<10	<1	45
Standard:																													
Pb113A		11.6	0.29	40	55	<5	1.60	45	3	5	2319	1.14	<10	0.11	1533	68	0.02	3	90	5596	15	<20	83	0.02	<10	7	<10	<1	6971

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
df/5655
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5656

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

20-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07160
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09797	1.13	0.033
2	X09798	0.93	0.027
3	X09799	1.11	0.032
4	X09800	2.14	0.062
5	X09801	0.63	0.018
6	X09802	2.70	0.079
7	X09803	1.17	0.034
8	X09804	2.19	0.064
9	X09805	0.81	0.024
10	X09806	0.44	0.013
11	X09807	0.48	0.014
12	X09808	1.03	0.030
13	X09809	0.38	0.011
14	X09810	0.83	0.024
15	X09811	0.65	0.019
16	X09812	<0.03	<0.001
17	X09813	0.77	0.022
18	X09814	0.96	0.028
19	X09815	0.63	0.018
20	X09816	0.47	0.014
21	X09817	0.91	0.027
22	X09818	0.59	0.017
23	X09819	0.73	0.021
24	X09820	0.73	0.021
25	X09821	0.94	0.027

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5656 20-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X09822	0.88	0.026
27	X09823	0.94	0.027
28	X09824	0.98	0.029
29	X09825	0.36	0.010
30	X09826	0.37	0.011
31	X09827	0.50	0.015
32	X09828	0.55	0.016
33	X09829	0.52	0.015
34	X09830	0.78	0.023
35	X09831	1.01	0.029
QC DATA:			
Repeat:			
1	X09797	1.10	0.032
10	X09806	0.42	0.012
19	X09815	0.59	0.017
Resplits:			
1	X09797	1.01	0.029
Standard:			
OXK48		3.51	0.102

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

21-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5656

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07160
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09797	2.8	0.63	<5	30	<5	1.97	3	10	94	3234	3.43	<10	0.58	996	11	<0.01	5	890	56	10	<20	77	0.03	<10	10	<10	3	119
2	X09798	1.8	1.14	<5	40	<5	1.73	2	8	46	2306	2.98	<10	1.03	1454	10	<0.01	2	980	24	15	<20	44	0.04	<10	11	<10	2	128
3	X09799	2.5	1.28	<5	40	<5	0.42	2	10	53	1899	4.20	<10	0.94	441	16	<0.01	6	1090	136	15	<20	20	0.04	<10	10	<10	3	169
4	X09800	3.1	1.25	5	30	<5	1.19	3	11	51	2238	3.94	<10	0.92	739	16	0.01	5	980	52	25	<20	106	0.03	<10	14	<10	1	177
5	X09801	2.1	0.77	<5	35	<5	1.28	3	10	83	2429	3.17	<10	0.64	1056	24	0.01	6	870	32	15	<20	104	0.04	<10	11	<10	2	113
6	X09802	3.4	0.36	5	20	<5	0.62	7	11	84	3599	3.27	<10	0.19	398	22	<0.01	3	880	70	5	<20	43	0.03	<10	5	<10	<1	93
7	X09803	1.9	0.81	15	25	<5	1.29	2	9	51	2276	3.10	<10	0.69	1260	14	<0.01	4	1030	30	10	<20	19	0.03	<10	9	<10	2	150
8	X09804	1.7	1.19	<5	40	<5	1.34	2	9	58	1673	3.46	<10	1.19	1227	13	0.01	5	1030	38	20	<20	58	0.04	<10	14	<10	3	136
9	X09805	2.1	1.21	<5	55	<5	1.18	2	9	57	1833	2.85	<10	1.01	778	18	<0.01	3	1050	54	15	<20	42	0.04	<10	10	<10	3	170
10	X09806	2.0	0.28	<5	25	<5	1.90	5	9	75	1143	3.09	<10	0.48	1412	23	<0.01	5	900	106	10	<20	36	0.03	<10	8	<10	2	81
11	X09807	1.7	0.40	<5	35	<5	2.68	2	7	51	1627	2.00	<10	0.74	1585	15	<0.01	3	980	32	15	<20	164	0.04	<10	11	<10	5	38
12	X09808	3.7	1.21	50	50	<5	0.74	4	16	57	3344	3.88	20	0.56	280	213	0.03	17	430	132	45	<20	38	0.04	<10	45	<10	6	148
13	X09809	1.1	0.58	<5	40	<5	3.28	2	8	48	1134	2.38	<10	0.64	1016	20	0.01	3	1040	32	10	<20	314	0.03	<10	14	<10	4	69
14	X09810	1.8	0.68	<5	35	<5	3.29	2	9	61	2282	2.79	<10	0.69	920	12	0.01	4	990	42	10	<20	294	0.03	<10	15	<10	3	93
15	X09811	1.3	0.76	<5	60	<5	3.14	6	8	49	1471	3.25	<10	0.81	1321	17	0.02	5	990	48	15	<20	269	0.05	<10	18	<10	3	204
16	X09812	<0.2	1.11	<5	265	20	0.59	<1	7	94	9	2.21	<10	0.67	562	2	0.10	6	950	16	10	<20	97	0.11	<10	48	<10	2	43
17	X09813	2.0	0.63	<5	30	<5	1.61	2	9	72	2646	3.55	<10	0.75	1435	13	<0.01	6	890	54	15	<20	43	0.04	<10	12	<10	3	78
18	X09814	2.4	0.77	<5	45	<5	1.74	2	9	60	3183	3.07	<10	0.87	1215	12	<0.01	6	900	32	20	<20	55	0.04	<10	12	<10	4	96
19	X09815	1.9	1.05	<5	35	<5	2.30	2	10	69	1656	3.78	<10	0.85	1065	20	<0.01	6	1060	44	20	<20	63	0.04	<10	14	<10	2	145
20	X09816	2.0	1.09	<5	45	<5	2.03	1	9	57	1508	3.10	<10	1.11	1412	16	<0.01	3	990	30	10	<20	74	0.04	<10	16	<10	3	141
21	X09817	2.8	1.36	<5	45	<5	0.76	3	12	95	2126	4.78	<10	0.97	853	21	<0.01	8	950	24	25	<20	27	0.04	<10	16	<10	1	168
22	X09818	3.4	0.31	15	30	<5	0.25	3	11	97	1630	3.83	<10	<0.01	53	21	<0.01	8	980	86	20	<20	23	0.02	10	8	<10	1	41
23	X09819	1.8	0.25	<5	25	<5	0.18	5	9	141	2067	3.33	<10	<0.01	36	12	<0.01	6	690	58	<5	<20	17	0.04	<10	6	<10	<1	188
24	X09820	6.3	0.21	<5	25	<5	0.23	6	12	168	6574	4.73	<10	0.01	154	14	0.01	8	350	110	10	<20	28	0.02	<10	4	<10	<1	149
25	X09821	2.7	0.30	<5	20	<5	1.12	4	9	126	3305	3.46	<10	0.39	1041	13	<0.01	7	290	30	10	<20	35	0.03	<10	8	<10	<1	144

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09822	2.3	0.37	<5	25	<5	1.15	2	10	112	2989	4.21	<10	0.50	1031	9	<0.01	5	350	30	10	<20	37	0.04	<10	9	<10	<1	52
27	X09823	2.1	0.46	<5	35	<5	1.52	2	9	115	2693	3.55	<10	0.60	880	10	<0.01	5	540	36	<5	<20	29	0.03	<10	9	<10	<1	73
28	X09824	2.7	0.30	<5	30	<5	1.93	2	10	118	2774	3.58	<10	0.40	809	14	<0.01	5	420	40	10	<20	103	0.04	<10	8	<10	1	54
29	X09825	2.9	0.19	55	30	<5	0.52	2	10	132	2836	4.85	<10	0.11	433	12	<0.01	7	300	40	25	<20	20	0.04	<10	3	<10	<1	40
30	X09826	1.8	0.30	<5	35	<5	1.38	2	11	124	1908	3.88	<10	0.46	977	107	<0.01	6	630	30	10	<20	33	0.04	<10	5	<10	<1	50
31	X09827	1.8	0.23	<5	35	<5	0.66	2	11	118	2232	4.11	<10	0.15	451	10	<0.01	6	520	36	<5	<20	22	0.03	<10	5	<10	<1	32
32	X09828	2.0	0.30	<5	25	<5	0.46	4	10	130	2063	4.74	<10	0.13	296	36	<0.01	7	580	38	<5	<20	15	0.04	<10	4	<10	<1	169
33	X09829	2.3	0.23	<5	30	<5	1.11	5	9	123	2573	4.41	<10	0.20	590	11	<0.01	8	570	84	15	<20	32	0.03	<10	5	<10	<1	209
34	X09830	2.4	0.34	<5	25	<5	1.14	3	10	173	2244	4.41	<10	0.30	562	9	0.01	7	430	50	5	<20	39	0.04	<10	8	<10	<1	106
35	X09831	1.9	0.49	<5	35	<5	1.79	1	9	144	2207	3.70	<10	0.56	1112	10	0.01	7	430	22	5	<20	62	0.04	<10	8	<10	2	66
QC DATA:																													
Repeat:																													
1	X09797	2.9	0.62	<5	35	<5	1.96	3	10	91	3268	3.40	<10	0.58	994	12	<0.01	5	880	58	15	<20	74	0.03	<10	10	<10	3	117
10	X09806	2.1	0.25	<5	35	<5	1.85	4	9	71	1084	2.99	<10	0.45	1369	20	<0.01	3	890	106	5	<20	40	0.04	<10	8	<10	3	79
19	X09815	1.8	1.02	<5	35	<5	2.29	2	10	66	1653	3.75	<10	0.84	1062	20	<0.01	6	1050	44	20	<20	68	0.04	<10	13	<10	2	144
Resplit:																													
1	X09797	2.8	0.70	<5	35	<5	1.89	3	11	96	3080	3.59	<10	0.60	988	13	<0.01	6	1010	62	10	<20	79	0.03	<10	11	<10	3	129
Standard:																													
Pb113A		11.4	0.28	65	55	<5	1.73	44	2	5	2282	1.09	<10	0.11	1485	61	0.02	4	70	5606	15	<20	65	0.02	<10	7	<10	<1	7030

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
df/5656
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5657

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

20-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07161
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09832	0.59	0.017
2	X09833	0.72	0.021
3	X09834	0.95	0.028
4	X09835	0.62	0.018
5	X09836	1.43	0.042
6	X09837	1.01	0.029
7	X09838	0.70	0.020
8	X09839	0.66	0.019
9	X09840	0.51	0.015
10	X09841	0.60	0.017
11	X09842	0.72	0.021
12	X09843	0.65	0.019
13	X09844	0.65	0.019
14	X09845	0.54	0.016
15	X09846	1.30	0.038
16	X09847	1.22	0.036
17	X09848	1.16	0.034
18	X09849	1.13	0.033
19	X09850	1.29	0.038
20	X09851	<0.03	<0.001
21	X09852	2.70	0.079
22	X09853	3.40	0.099
23	X09854	1.32	0.038
24	X09855	0.96	0.028
25	X09856	1.10	0.032

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5657 20-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	X09857	1.15	0.034
27	X09858	1.26	0.037
28	X09859	2.90	0.085
29	X09860	1.46	0.043
30	X09861	1.45	0.042
31	X09862	1.00	0.029
32	X09863	1.47	0.043
33	X09864	1.17	0.034
34	X09865	0.88	0.026
35	X09866	1.52	0.044
QC DATA:			
Repeat:			
1	X09832	0.49	0.014
10	X09841	0.57	0.017
19	X09850	1.28	0.037
21	X09852	2.80	0.082
22	X09853	3.70	0.108
28	X09859	2.74	0.080
Resplits:			
1	X09832	0.51	0.015
Standard:			
OXi54		1.87	0.055

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

21-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5657

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07161
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09832	2.7	0.40	10	35	<5	2.09	6	9	77	1390	3.07	<10	0.42	1248	15	0.01	1	1060	68	<5	<20	75	<0.01	<10	5	<10	5	204
2	X09833	1.4	0.59	15	35	<5	1.47	2	9	67	1188	3.51	<10	0.63	1353	21	0.01	1	1090	26	<5	<20	36	<0.01	<10	7	<10	5	101
3	X09834	1.8	0.95	20	40	<5	0.95	2	8	82	1379	3.98	<10	0.73	852	17	0.01	<1	1060	14	<5	<20	42	<0.01	<10	7	<10	4	123
4	X09835	2.2	0.40	15	40	<5	2.40	2	9	113	1854	3.33	<10	0.63	1823	13	0.01	2	870	52	<5	<20	53	<0.01	<10	8	<10	6	49
5	X09836	2.2	0.97	15	35	<5	0.97	3	11	95	2542	4.28	<10	0.89	983	12	0.01	<1	860	38	<5	<20	38	<0.01	<10	11	<10	4	135
6	X09837	1.9	1.94	25	50	<5	0.47	3	9	100	2028	5.53	<10	1.58	817	9	0.02	<1	1110	14	<5	<20	30	<0.01	<10	16	<10	4	267
7	X09838	1.4	1.38	20	75	<5	1.18	2	8	96	1340	3.85	<10	1.02	990	12	0.02	2	1150	12	<5	<20	48	<0.01	<10	14	<10	5	190
8	X09839	1.4	0.86	10	40	<5	1.07	2	10	95	1007	4.39	<10	0.55	618	13	0.02	<1	1070	26	<5	<20	64	<0.01	<10	15	<10	4	104
9	X09840	1.3	0.95	10	65	<5	1.55	2	9	93	992	3.96	<10	0.65	791	18	0.03	1	1100	18	<5	<20	100	<0.01	<10	22	<10	4	151
10	X09841	1.3	0.98	10	60	<5	1.87	3	10	86	1106	4.22	<10	0.68	904	19	0.03	<1	1110	20	<5	<20	107	<0.01	<10	23	<10	4	146
11	X09842	1.5	0.76	10	55	<5	2.27	2	8	88	1789	3.68	<10	0.50	617	15	0.03	<1	1010	18	<5	<20	218	<0.01	<10	21	<10	4	97
12	X09843	1.5	0.71	5	60	<5	2.82	2	7	110	1581	3.75	<10	0.40	546	13	0.03	1	1020	12	<5	<20	270	<0.01	<10	24	<10	4	78
13	X09844	1.5	0.59	10	45	<5	2.93	2	8	83	1604	3.50	<10	0.34	489	16	0.02	<1	1000	18	<5	<20	313	<0.01	<10	18	<10	4	72
14	X09845	1.3	0.68	10	45	<5	2.84	2	9	102	1437	3.61	<10	0.38	402	112	0.03	1	1000	16	<5	<20	321	<0.01	<10	19	<10	4	73
15	X09846	3.0	0.35	25	35	<5	0.24	2	8	213	2337	4.22	<10	0.05	94	13	0.01	4	960	24	<5	<20	18	<0.01	<10	7	<10	2	36
16	X09847	3.9	0.55	35	35	<5	0.18	2	11	223	2730	4.94	<10	0.14	329	8	0.02	4	790	22	<5	<20	14	<0.01	<10	11	<10	2	38
17	X09848	4.0	0.24	50	35	<5	0.14	3	10	168	2805	5.46	<10	0.01	35	11	0.02	2	720	64	<5	<20	10	<0.01	<10	6	<10	1	65
18	X09849	3.6	0.49	20	40	<5	0.25	3	10	206	3062	5.03	<10	0.15	237	10	0.01	3	720	26	<5	<20	20	<0.01	<10	10	<10	2	59
19	X09850	3.2	0.57	45	40	<5	0.17	3	10	186	3182	5.70	<10	0.18	271	10	0.01	2	870	16	<5	<20	8	<0.01	<10	10	<10	2	57
20	X09851	<0.2	1.14	10	275	<5	0.65	<1	7	100	9	2.27	<10	0.59	579	<1	0.11	8	970	10	<5	<20	98	0.15	<10	41	<10	5	45
21	X09852	3.7	0.33	90	45	5	0.16	5	13	208	2349	8.69	<10	0.04	74	9	0.02	2	850	28	<5	<20	9	<0.01	<10	6	<10	1	77
22	X09853	4.5	0.26	115	45	10	0.18	4	11	170	1605	8.46	<10	0.01	38	12	0.02	<1	1060	50	15	<20	10	<0.01	<10	6	<10	2	61
23	X09854	4.5	0.48	60	35	<5	0.30	5	12	161	3359	5.52	<10	0.13	155	15	0.01	2	1180	24	<5	<20	15	<0.01	<10	6	<10	4	145
24	X09855	4.4	0.28	10	30	<5	0.15	2	10	191	3653	4.28	<10	0.03	43	18	0.01	3	770	18	<5	<20	26	<0.01	<10	4	<10	2	17
25	X09856	2.3	0.24	15	30	<5	0.10	2	7	244	1527	3.33	<10	0.02	41	24	0.01	4	490	16	<5	<20	12	<0.01	<10	4	<10	1	11

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09857	4.2	0.24	30	35	<5	0.14	2	11	170	2901	4.34	<10	0.01	41	13	0.01	2	720	34	10	<20	74	<0.01	<10	4	<10	2	16
27	X09858	5.5	0.31	90	40	<5	0.19	3	12	174	3551	6.46	<10	0.01	37	10	0.02	2	930	36	55	<20	10	<0.01	<10	5	<10	2	39
28	X09859	4.4	0.27	40	35	<5	0.20	3	9	148	3403	5.50	<10	0.02	31	8	0.01	1	1020	20	10	<20	8	<0.01	<10	3	<10	3	30
29	X09860	4.0	0.61	35	40	<5	0.31	2	8	154	3648	4.59	<10	0.29	333	10	0.01	2	800	16	<5	<20	15	<0.01	<10	6	<10	3	38
30	X09861	3.9	0.61	30	40	<5	0.18	3	13	138	4039	5.84	<10	0.26	230	11	0.01	<1	780	24	<5	<20	9	<0.01	<10	5	<10	2	55
31	X09862	3.2	1.11	65	70	5	0.73	4	14	58	3290	3.90	20	0.48	273	205	0.03	16	610	123	30	<20	42	0.03	<10	35	<10	8	160
32	X09863	6.4	0.55	50	40	5	0.21	3	10	195	3487	6.10	<10	0.16	154	53	0.01	2	950	258	<5	<20	10	<0.01	<10	7	<10	3	37
33	X09864	3.8	0.84	40	45	<5	0.18	3	7	159	3477	5.11	<10	0.40	286	16	0.01	1	710	16	<5	<20	10	<0.01	<10	10	<10	2	60
34	X09865	2.8	0.95	20	45	<5	0.71	2	7	130	2542	4.64	<10	0.56	610	11	0.01	1	850	28	<5	<20	41	<0.01	<10	9	<10	3	51
35	X09866	5.8	0.76	25	50	<5	0.87	4	11	101	6327	6.46	<10	0.34	532	8	0.02	<1	820	34	<5	<20	52	<0.01	<10	11	<10	2	54
QC DATA:																													
Repeat:																													
1	X09832	2.7	0.46	10	35	<5	2.17	6	9	84	1469	3.26	<10	0.44	1319	19	0.01	1	1130	72	<5	<20	79	<0.01	<10	6	<10	5	216
10	X09841	1.3	0.97	10	70	<5	1.85	3	10	87	1074	4.08	<10	0.65	896	19	0.03	1	1080	20	<5	<20	110	<0.01	<10	23	<10	4	146
19	X09850	3.2	0.58	45	40	<5	0.17	3	10	191	3101	5.71	<10	0.18	262	10	0.01	2	850	14	<5	<20	9	<0.01	<10	10	<10	2	60
Resplit:																													
1	X09832	2.8	0.41	10	35	<5	2.05	7	8	77	1492	3.13	<10	0.42	1263	20	0.01	1	1100	74	<5	<20	75	<0.01	<10	6	<10	5	209
Standard:																													
Pb113A		11.8	0.27	55	70	<5	1.79	40	2	3	2344	1.05	<10	0.11	1476	59	0.02	2	70	5600	10	<20	92	0.01	<10	5	<10	1	6895

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
dl/n5657
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5658

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

12-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09867	1.05	0.031
2	X09868	1.10	0.032
3	X09869	1.12	0.033
4	X09870	0.92	0.027
5	X09871	0.86	0.025
6	X09872	0.87	0.025
7	X09873	1.27	0.037
8	X09874	1.15	0.034
9	X09875	1.29	0.038
10	X09876	0.74	0.022
11	X09877	1.23	0.036
12	X09878	0.74	0.022
13	X09879	0.78	0.023
14	X09880	0.69	0.020
15	X09881	0.79	0.023
16	X09882	0.74	0.022
17	X09883	0.70	0.020
18	X09884	0.72	0.021
19	X09885	0.34	0.010
20	X09886	0.51	0.015
21	X09887	0.62	0.018
22	X09888	1.82	0.053
23	X09889	0.73	0.021
24	X09890	1.02	0.030
25	X09891	1.11	0.032
26	X09892	0.94	0.027

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7 - 5658

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	X09893	1.07	0.031
28	X09894	<0.03	<0.001
29	X09895	0.76	0.022
30	X09896	0.61	0.018
31	X09897	0.69	0.020
32	X09898	0.71	0.021
33	X09899	0.52	0.015
34	X09900	0.43	0.013
35	X09901	1.11	0.032

QC DATA:

Repeat:

1	X09867	1.06	0.031
10	X09876	0.69	0.020
19	X09885	0.37	0.011

Resplits:

1	X09867	1.15	0.034

Standard:

OXI54		1.87	0.055

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
XLS/07

11-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5658

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09867	3.0	0.38	25	40	<5	1.07	3	14	128	2616	4.35	<10	0.12	522	18	<0.01	5	570	28	5	<20	67	0.01	<10	6	<10	<1	35
2	X09868	3.6	0.42	30	45	<5	0.59	3	12	132	3130	4.65	<10	0.11	263	14	<0.01	6	530	34	<5	<20	35	0.01	<10	7	<10	<1	34
3	X09869	4.2	0.42	10	55	<5	0.76	2	12	143	3330	4.76	<10	0.10	376	15	<0.01	4	640	38	<5	<20	54	0.02	<10	6	<10	1	27
4	X09870	3.0	0.56	20	45	<5	0.97	3	13	133	2820	4.78	<10	0.20	530	18	<0.01	7	630	40	10	<20	56	<0.01	<10	8	<10	<1	34
5	X09871	2.7	0.64	10	55	<5	1.18	2	10	150	2458	4.01	<10	0.29	581	19	<0.01	4	640	28	<5	<20	81	0.01	<10	8	<10	<1	47
6	X09872	2.8	0.93	<5	55	<5	1.40	2	12	131	2731	4.91	<10	0.52	699	14	<0.01	5	540	32	5	<20	94	0.01	<10	12	<10	<1	56
7	X09873	4.0	0.60	35	50	<5	0.68	3	11	147	3200	5.45	<10	0.19	387	13	<0.01	4	540	32	<5	<20	37	0.01	<10	8	<10	<1	35
8	X09874	3.6	0.74	35	55	<5	0.47	3	13	113	2995	6.00	<10	0.28	311	18	<0.01	4	650	30	<5	<20	23	0.01	<10	9	<10	<1	41
9	X09875	4.1	0.40	15	45	<5	0.78	1	10	140	4465	4.37	<10	0.13	447	10	<0.01	5	350	24	<5	<20	53	0.01	<10	6	<10	<1	25
10	X09876	3.7	0.84	<5	50	<5	0.45	1	10	124	3718	4.61	<10	0.55	512	11	<0.01	4	530	36	<5	<20	27	0.02	<10	11	<10	<1	49
11	X09877	4.7	0.90	<5	55	<5	0.88	2	14	104	5431	4.72	<10	0.58	738	12	<0.01	4	320	34	<5	<20	70	0.01	<10	11	<10	<1	44
12	X09878	3.1	0.94	<5	45	<5	0.80	2	10	115	2632	4.49	<10	0.62	616	12	<0.01	4	700	30	<5	<20	44	0.01	<10	10	<10	<1	46
13	X09879	3.7	0.92	<5	50	<5	1.14	2	11	118	3449	4.44	<10	0.62	721	22	<0.01	5	680	28	10	<20	76	0.01	<10	11	<10	1	46
14	X09880	3.2	0.42	<5	55	<5	0.33	2	11	133	2610	5.78	<10	0.11	207	19	<0.01	6	460	36	<5	<20	31	0.01	<10	7	<10	<1	18
15	X09881	2.6	0.96	20	55	<5	0.45	2	9	119	2168	3.97	<10	0.55	402	19	<0.01	5	750	26	10	<20	34	<0.01	<10	13	<10	<1	48
16	X09882	2.6	1.09	<5	45	<5	0.36	2	10	151	2211	5.07	<10	0.66	406	16	<0.01	6	600	32	5	<20	24	0.01	<10	15	<10	<1	63
17	X09883	2.9	1.02	<5	55	<5	0.39	2	10	145	2422	4.72	<10	0.62	409	12	<0.01	6	640	30	10	<20	36	0.01	<10	14	<10	<1	62
18	X09884	3.1	0.46	<5	55	<5	0.19	2	10	144	2421	5.40	<10	0.16	150	12	<0.01	5	400	30	<5	<20	24	0.01	<10	7	<10	<1	28
19	X09885	2.5	0.35	<5	45	<5	0.30	1	7	185	2293	3.21	<10	0.16	220	10	<0.01	5	120	22	<5	<20	33	<0.01	<10	6	<10	<1	19
20	X09886	3.1	0.87	<5	35	<5	0.97	2	9	133	2656	4.17	<10	0.58	587	15	<0.01	5	580	28	10	<20	85	0.01	<10	12	<10	<1	50
21	X09887	4.1	0.93	<5	40	<5	0.81	2	11	124	2613	4.41	<10	0.62	550	21	<0.01	5	660	42	<5	<20	74	0.02	<10	12	<10	<1	59
22	X09888	3.9	1.13	20	65	<5	1.01	2	22	58	8578	4.27	20	0.62	197	617	0.04	61	50	72	25	<20	56	0.04	<10	43	<10	3	72
23	X09889	4.7	1.06	15	50	<5	0.29	2	10	141	2205	5.07	<10	0.67	281	22	<0.01	4	900	38	<5	<20	19	0.02	<10	16	<10	<1	63
24	X09890	6.0	0.53	<5	75	<5	0.42	4	17	146	4954	>10	<10	0.20	320	67	<0.01	8	240	76	<5	<20	29	0.02	<10	13	<10	<1	34
25	X09891	3.6	0.98	<5	45	<5	0.37	3	11	161	3396	4.56	<10	0.57	394	20	<0.01	10	610	36	30	<20	29	<0.01	<10	15	<10	<1	60

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09892	3.7	1.00	<5	45	<5	0.81	1	12	141	3383	4.88	<10	0.67	582	12	<0.01	4	650	34	<5	<20	64	0.02	<10	17	<10	<1	57
27	X09893	5.1	0.47	<5	45	<5	0.30	2	12	163	4220	4.30	<10	0.22	242	12	<0.01	6	300	34	5	<20	23	<0.01	<10	9	<10	<1	29
28	X09894	<0.2	1.00	<5	265	15	0.63	<1	7	98	10	2.17	<10	0.66	515	1	0.10	4	890	20	<5	<20	82	0.13	<10	45	<10	2	42
29	X09895	3.9	1.12	<5	70	<5	1.14	2	11	127	3217	4.43	<10	0.78	739	25	<0.01	5	790	44	10	<20	105	0.01	<10	20	<10	1	58
30	X09896	3.2	1.13	<5	85	<5	1.28	1	9	122	2145	3.76	<10	0.77	793	26	<0.01	4	850	40	5	<20	127	0.02	<10	17	<10	2	60
31	X09897	3.0	1.01	<5	65	<5	2.02	2	10	112	2295	3.65	<10	0.69	1045	13	<0.01	4	820	34	10	<20	173	0.02	<10	17	<10	2	54
32	X09898	2.9	0.80	<5	50	<5	1.54	3	10	109	2162	3.54	<10	0.63	951	11	<0.01	4	790	98	<5	<20	113	0.02	<10	13	<10	1	82
33	X09899	1.6	1.40	<5	95	<5	1.80	1	9	90	1425	4.06	<10	1.17	1252	16	<0.01	4	1010	38	10	<20	129	0.02	<10	21	<10	1	85
34	X09900	2.6	0.96	<5	75	<5	1.44	2	9	119	1913	3.60	<10	0.73	910	106	<0.01	3	850	32	10	<20	85	0.02	<10	13	<10	1	52
35	X09901	3.6	1.05	<5	65	<5	1.35	1	13	144	3409	4.23	<10	0.70	760	12	<0.01	5	670	34	10	<20	87	0.01	<10	16	<10	2	55
QC DATA:																													
Repeat:																													
1	X09867	3.0	0.40	25	50	<5	1.05	2	13	130	2562	4.31	<10	0.11	512	20	<0.01	5	540	26	<5	<20	65	0.01	<10	6	<10	<1	34
10	X09876	3.9	0.86	<5	50	<5	0.46	2	10	131	3767	4.71	<10	0.56	525	12	<0.01	5	550	38	<5	<20	28	0.01	<10	11	<10	<1	50
19	X09885	2.6	0.36	<5	50	<5	0.29	<1	7	190	2281	3.19	<10	0.16	218	10	<0.01	6	110	20	<5	<20	35	0.02	<10	6	<10	<1	19
Resplit:																													
1	X09867	2.8	0.40	30	35	<5	0.92	1	7	131	2640	4.34	10	0.15	503	20	<0.01	11	520	26	5	<20	61	<0.01	<10	10	<10	<1	35
Standard:																													
PB113A		11.3	0.26	45	70	<5	1.62	37	6	11	2270	1.02	10	0.12	1462	66	0.02	3	90	5652	15	<20	80	0.01	<10	33	<10	2	6938

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5652S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5659

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

12-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	X09902	1.02	0.030		
2	X09903	1.13	0.033		
3	X09904	1.02	0.030		
4	X09905	0.75	0.022		
5	X09906	0.68	0.020		
6	X09907	0.80	0.023		
7	X09908	0.67	0.020	50.0	1.46
8	X09909	0.47	0.014	34.0	0.99
9	X09910	0.52	0.015	82.0	2.39
10	X09911	0.66	0.019	66.0	1.93
11	X09912	0.73	0.021		
12	X09913	0.73	0.021		
13	X09914	1.82	0.053		
14	X09915	1.14	0.033		
15	X09916	0.86	<0.001		
16	X09917	0.91	0.027		
17	X09918	<0.03	<0.001		
18	X09919	0.69	0.020		
19	X09920	1.05	0.031		
20	X09921	0.70	0.020		
21	X09922	0.89	0.026		
22	X09923	0.82	0.024		
23	X09924	0.90	0.026		
24	X09925	0.85	0.025		
25	X09926	0.91	0.027		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7 - 5659

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
26	X09927	0.63	0.018		
27	X09928	0.42	0.012		
28	X09929	0.51	0.015		
29	X09930	0.57	0.017		
30	X09931	0.28	0.008		
31	X09932	0.89	0.026		
32	X09933	0.59	0.017		
33	X09934	1.09	0.032		
34	X09935	0.50	0.015		
35	X09936	0.80	0.023		
QC DATA:					
Repeat:					
1	X09902	0.94	0.027		
2	X09903	1.19	0.035		
10	X09911	0.60	0.017		
14	X09915	1.18	0.034		
16	X09917	0.97	0.028		
19	X09920	1.12	0.033		
24	X09925	0.82	0.024		
Resplits:					
1	X09902	1.18	0.034		
Standard:					
OXI54		1.86	0.054		
PB113				22.7	0.66

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
XLS/07

11-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5659

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09902	3.9	0.98	<5	55	<5	0.96	1	11	86	3248	4.04	<10	0.78	722	11	<0.01	3	800	32	10	<20	65	0.01	<10	12	<10	1	43
2	X09903	4.3	1.10	<5	60	<5	1.23	2	11	119	3725	3.84	<10	1.00	770	13	<0.01	4	680	40	10	<20	102	0.01	<10	16	<10	1	43
3	X09904	4.8	0.85	<5	55	<5	1.65	2	11	103	3996	4.00	<10	0.70	873	19	<0.01	4	710	22	10	<20	198	0.01	<10	14	<10	2	52
4	X09905	6.9	0.23	15	45	<5	0.48	2	13	169	7778	3.75	<10	0.01	221	25	0.01	6	<10	48	<5	<20	54	<0.01	<10	5	<10	<1	48
5	X09906	4.4	0.66	<5	50	<5	0.77	2	16	124	3820	4.76	<10	0.43	500	14	<0.01	5	550	36	<5	<20	64	0.01	<10	11	<10	<1	39
6	X09907	5.6	0.54	65	55	<5	1.51	4	9	132	2260	3.68	<10	0.30	814	13	<0.01	4	870	40	<5	<20	78	0.01	<10	9	<10	2	63
7	X09908	>30	0.25	80	50	<5	0.64	7	13	124	2264	6.26	<10	0.04	369	18	<0.01	5	810	116	80	<20	28	0.02	<10	7	<10	<1	276
8	X09909	>30	0.27	185	45	<5	0.33	6	14	136	1858	5.77	<10	<0.01	145	53	<0.01	5	770	52	275	<20	15	0.01	<10	7	<10	<1	154
9	X09910	>30	0.21	425	55	<5	0.69	10	12	126	2425	5.70	<10	<0.01	386	15	<0.01	5	770	100	455	<20	43	0.01	<10	7	<10	<1	181
10	X09911	>30	0.32	285	50	<5	0.57	9	12	120	2124	5.52	<10	<0.01	256	14	<0.01	5	1050	60	200	<20	42	0.01	<10	9	<10	<1	141
11	X09912	5.1	0.72	10	50	<5	0.96	2	10	114	2216	4.37	<10	0.43	496	23	<0.01	6	830	28	20	<20	62	0.01	<10	12	<10	<1	38
12	X09913	2.4	0.83	<5	70	<5	2.07	1	10	107	1879	3.31	<10	0.44	629	11	0.01	3	900	32	10	<20	232	0.02	<10	16	<10	1	41
13	X09914	3.9	1.13	20	65	<5	1.01	3	21	59	8517	4.15	20	0.62	196	592	0.04	61	80	72	25	<20	54	0.04	<10	44	<10	3	72
14	X09915	3.4	1.09	<5	70	<5	1.80	1	11	88	3195	4.00	<10	0.77	746	15	<0.01	4	780	34	10	<20	173	0.01	<10	17	<10	<1	52
15	X09916	3.0	1.29	10	65	<5	1.59	2	10	93	1715	4.86	<10	0.97	944	15	<0.01	4	990	42	10	<20	120	0.02	<10	20	<10	1	63
16	X09917	5.6	0.46	85	55	<5	1.66	13	10	113	1129	4.86	<10	0.32	1061	17	<0.01	4	830	46	5	<20	108	0.03	<10	9	<10	1	190
17	X09918	<0.2	1.13	5	270	10	0.64	<1	7	90	8	2.33	10	0.62	544	2	0.11	6	970	26	<5	<20	90	0.14	<10	48	<10	2	45
18	X09919	3.2	0.62	75	45	<5	0.86	4	13	105	968	4.61	<10	0.29	508	15	<0.01	5	1180	36	10	<20	52	0.02	<10	14	<10	1	43
19	X09920	7.6	0.39	45	45	<5	1.30	3	10	133	2558	4.67	<10	0.20	726	31	<0.01	5	800	30	5	<20	71	0.01	<10	8	<10	1	36
20	X09921	6.9	0.37	70	55	<5	1.34	3	9	195	2791	3.81	<10	0.46	1088	14	<0.01	6	470	48	20	<20	67	0.02	<10	8	<10	1	53
21	X09922	3.7	1.21	<5	75	<5	1.08	2	9	130	2454	3.54	<10	1.16	905	21	<0.01	5	950	32	15	<20	74	0.02	<10	20	<10	2	93
22	X09923	5.0	1.00	5	65	<5	1.12	2	10	141	3029	3.51	<10	0.92	804	44	<0.01	6	810	34	20	<20	82	<0.01	<10	18	<10	2	67
23	X09924	4.1	0.94	<5	55	<5	1.88	2	18	98	3149	4.17	<10	0.77	899	93	<0.01	3	780	44	10	<20	158	0.01	<10	17	<10	2	63
24	X09925	2.8	0.77	<5	45	<5	1.91	1	14	93	2441	4.37	<10	0.61	845	54	<0.01	4	820	48	10	<20	152	0.02	<10	13	<10	2	47
25	X09926	2.7	0.84	<5	65	<5	1.93	<1	10	84	2800	3.39	<10	0.67	846	55	<0.01	3	890	32	5	<20	151	0.01	<10	16	<10	3	54

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007-5659 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09927	2.0	0.90	<5	60	<5	1.86	1	13	116	2087	3.77	<10	0.77	892	18	<0.01	5	900	38	10	<20	133	0.02	<10	16	<10	2	47
27	X09928	1.6	0.80	<5	65	<5	2.51	1	8	64	1527	3.16	<10	0.64	1015	17	<0.01	3	900	28	5	<20	207	0.02	<10	17	<10	2	51
28	X09929	1.8	0.88	<5	110	<5	2.53	1	9	68	1507	2.75	<10	0.67	1095	30	0.01	3	890	32	5	<20	223	0.02	<10	16	<10	2	68
29	X09930	2.5	0.72	<5	115	<5	2.02	1	7	76	2351	2.20	<10	0.54	776	29	0.01	2	790	26	<5	<20	181	0.01	<10	12	<10	2	51
30	X09931	2.0	0.98	<5	90	<5	1.96	1	9	71	1860	2.64	<10	0.85	1018	22	<0.01	3	840	30	10	<20	128	0.02	<10	13	<10	2	52
31	X09932	3.7	0.75	10	65	<5	1.06	1	8	128	3788	2.46	<10	0.79	701	27	<0.01	4	640	36	10	<20	70	<0.01	<10	11	<10	2	45
32	X09933	3.7	0.94	<5	80	<5	1.73	1	9	80	3605	2.55	<10	0.87	962	20	<0.01	3	690	36	15	<20	143	0.01	<10	13	<10	2	47
33	X09934	4.6	0.81	10	55	<5	2.15	2	11	68	3336	3.27	<10	0.93	1283	27	<0.01	4	650	34	15	<20	141	0.01	<10	13	<10	2	54
34	X09935	3.1	0.54	35	45	<5	2.27	2	11	88	1524	3.51	<10	0.29	976	41	<0.01	4	1010	50	5	<20	160	0.02	<10	10	<10	2	38
35	X09936	3.2	0.70	<5	75	<5	2.97	1	9	81	2207	2.41	<10	0.41	1070	27	<0.01	2	840	26	<5	<20	223	0.02	<10	11	<10	2	63
QC DATA:																													
Repeat:																													
1	X09902	3.9	1.01	<5	60	<5	0.97	1	11	83	3287	4.14	<10	0.83	736	13	<0.01	4	830	32	10	<20	61	0.01	<10	13	<10	1	44
10	X09911	>30	0.29	295	45	<5	0.57	9	12	114	2163	5.79	<10	<0.01	257	15	<0.01	5	1070	60	195	<20	37	0.01	<10	9	<10	<1	146
19	X09920	7.5	0.36	50	50	<5	1.29	3	10	126	2513	4.65	<10	0.20	725	33	<0.01	6	800	32	<5	<20	74	0.01	<10	8	<10	2	36
Resplit:																													
1	X09902	3.7	1.01	5	55	<5	0.97	2	11	90	3331	4.11	<10	0.82	738	12	<0.01	5	820	34	15	<20	56	0.01	<10	14	<10	1	43
Standard:																													
PB113A		11.9	0.22	50	60	<5	1.67	35	2	6	2323	1.04	<10	0.11	1485	62	0.02	3	80	5562	20	<20	83	0.01	<10	8	<10	<1	6988

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5652S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5662

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

22-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07164
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09937	0.43	0.013
2	X09938	0.93	0.027
3	X09939	1.23	0.036
4	X09940	1.00	0.029
5	X09941	0.73	0.021
6	X09942	0.45	0.013
7	X09943	0.45	0.013
8	X09944	0.33	0.010
9	X09945	0.56	0.016
10	X09946	0.92	0.027
11	X09947	0.37	0.011
12	X09948	0.74	0.022
13	X09949	0.71	0.021
14	X09950	0.76	0.022
15	X09951	0.53	0.015
16	X09952	0.75	0.022
17	X09953	0.31	0.009
18	X09954	0.51	0.015
19	X09955	0.72	0.021
20	X09956	0.46	0.013
21	X09957	<0.03	<0.001
22	X09958	0.38	0.011
23	X09959	0.36	0.010
24	X09960	0.29	0.008
25	X09961	0.40	0.012
26	X09962	0.79	0.023
27	X09963	0.46	0.013
28	X09964	0.32	0.009
29	X09965	0.34	0.010

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5662 22-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X09966	0.47	0.014
31	X09967	0.54	0.016
32	X09968	1.20	0.035
33	X09969	1.88	0.055
34	X09970	0.71	0.021
35	X09971	0.38	0.011

QC DATA:

Repeat:

1	X09937	0.40	0.012
10	X09946	0.86	0.025
19	X09955	0.90	0.026

Resplits:

1	X09937	0.37	0.011

Standard:

OXK48		3.60	0.105

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

22-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5662

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07164
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09937	2.6	0.86	<5	155	<5	3.15	<1	7	70	1392	2.15	<10	0.54	1222	44	<0.01	3	950	22	10	<20	220	0.01	<10	13	<10	4	67
2	X09938	2.8	0.89	10	95	<5	2.45	<1	9	88	2835	2.46	<10	0.63	956	25	<0.01	3	790	26	10	<20	159	0.01	<10	12	<10	4	47
3	X09939	3.8	0.82	<5	85	<5	2.04	1	9	113	4383	2.62	<10	0.58	740	16	<0.01	3	580	28	5	<20	158	<0.01	<10	14	<10	4	44
4	X09940	3.3	0.80	<5	80	<5	1.84	1	9	99	3603	3.37	<10	0.54	510	11	0.01	5	670	26	10	<20	157	<0.01	<10	23	<10	4	39
5	X09941	2.0	0.85	<5	120	<5	2.02	2	10	97	2323	3.49	<10	0.63	619	14	0.02	4	790	30	15	<20	200	0.01	<10	29	<10	4	49
6	X09942	2.1	0.80	10	130	<5	3.52	<1	9	96	2068	3.15	<10	0.58	1103	31	0.02	4	810	36	10	<20	379	0.01	<10	28	<10	9	47
7	X09943	0.6	0.88	20	60	<5	1.81	2	10	121	2005	3.61	<10	0.66	676	18	0.02	6	840	34	15	<20	153	<0.01	<10	21	<10	4	38
8	X09944	0.7	0.92	15	125	<5	2.50	<1	9	97	1584	2.77	<10	0.65	851	32	0.02	4	880	28	10	<20	208	0.01	<10	19	<10	5	51
9	X09945	2.7	1.06	10	70	<5	2.98	1	9	116	2158	3.15	<10	0.77	997	15	0.01	6	860	28	20	<20	207	0.01	<10	19	<10	5	46
10	X09946	3.1	0.81	20	65	<5	1.39	1	10	113	1341	4.17	<10	0.52	610	12	<0.01	5	1070	48	10	<20	78	0.01	<10	15	<10	4	45
11	X09947	1.4	0.98	<5	90	<5	2.63	2	9	89	984	3.44	10	0.69	726	19	<0.01	7	1040	38	25	<20	188	0.01	<10	22	<10	5	39
12	X09948	2.3	0.73	25	65	<5	2.31	5	10	99	1135	3.20	10	0.38	708	26	<0.01	5	1070	122	15	<20	131	0.01	<10	14	<10	4	98
13	X09949	2.1	0.77	15	50	<5	2.64	2	10	96	1243	3.00	10	0.44	803	26	<0.01	5	1060	36	10	<20	127	0.01	<10	13	<10	4	51
14	X09950	3.3	1.03	15	90	<5	2.69	2	9	97	2745	3.61	10	0.66	842	20	<0.01	5	740	42	20	<20	162	<0.01	<10	25	<10	5	55
15	X09951	2.7	0.68	10	70	<5	2.60	<1	9	77	1928	2.50	<10	0.42	734	21	<0.01	3	860	70	5	<20	161	0.01	<10	12	<10	6	52
16	X09952	5.4	0.49	35	50	<5	2.03	37	11	105	3096	3.53	<10	0.21	483	38	0.01	5	690	4098	15	<20	135	0.01	<10	10	<10	2	4304
17	X09953	3.0	1.27	40	55	<5	0.99	3	21	61	2711	3.50	20	0.68	196	205	0.03	11	420	58	15	<20	60	0.04	<10	50	<10	7	276
18	X09954	3.4	0.65	35	65	<5	1.73	17	10	71	2136	3.28	10	0.37	449	23	0.01	3	950	1362	<5	<20	142	<0.01	<10	14	<10	7	1430
19	X09955	4.3	0.60	<5	70	<5	2.74	1	12	111	4997	3.44	<10	0.33	763	11	0.01	5	510	58	10	<20	185	<0.01	<10	13	<10	7	49
20	X09956	1.1	0.86	<5	85	<5	3.95	1	11	99	1385	2.68	10	0.59	1065	10	<0.01	5	900	30	15	<20	227	0.05	<10	14	<10	6	56
21	X09957	<0.2	1.15	<5	285	20	0.63	<1	7	130	7	2.24	10	0.65	555	3	0.11	7	900	28	15	<20	103	0.13	<10	50	<10	7	43
22	X09958	1.3	0.93	5	140	<5	3.15	1	9	102	1202	2.58	10	0.59	878	13	<0.01	5	1030	26	15	<20	179	0.03	<10	17	<10	8	47
23	X09959	1.4	0.94	5	270	<5	2.76	1	8	75	1608	2.51	10	0.61	856	22	0.02	4	970	30	15	<20	168	0.05	<10	19	<10	8	47
24	X09960	1.4	0.72	<5	235	<5	2.65	1	8	76	1177	2.43	10	0.45	780	21	0.03	3	900	26	10	<20	228	0.07	<10	22	<10	9	40
25	X09961	1.4	0.79	15	120	<5	2.43	<1	9	63	1802	2.67	10	0.48	602	11	0.03	<1	780	30	<5	<20	350	0.07	<10	25	<10	6	39

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09962	2.7	0.82	<5	110	<5	1.45	4	21	68	3576	>10	20	0.55	464	26	0.03	10	440	34	20	<20	393	0.08	<10	133	<10	<1	57
27	X09963	1.0	0.82	<5	70	<5	2.37	3	14	96	1258	4.77	10	0.59	537	13	0.02	6	740	56	15	<20	195	0.06	<10	40	<10	4	38
28	X09964	0.9	0.95	<5	445	<5	2.11	2	7	82	893	4.17	10	0.70	600	10	0.02	6	1060	30	20	<20	143	0.07	<10	42	<10	6	45
29	X09965	0.7	0.84	5	280	<5	2.10	1	8	109	1049	3.51	10	0.57	553	9	0.02	5	1000	28	15	<20	97	0.07	<10	39	<10	7	37
30	X09966	1.1	0.83	<5	70	<5	2.77	1	11	101	1322	3.93	10	0.55	720	13	0.01	4	770	36	5	<20	164	0.06	<10	24	<10	6	34
31	X09967	1.0	0.99	<5	80	<5	1.84	2	9	106	1378	4.14	10	0.70	488	12	0.02	5	910	26	20	<20	87	0.07	<10	39	<10	7	41
32	X09968	3.1	0.80	5	75	<5	0.81	1	13	144	4151	4.89	10	0.51	289	12	0.02	5	400	38	5	<20	44	0.08	<10	48	<10	4	39
33	X09969	4.4	0.95	<5	110	<5	1.01	4	16	105	6533	6.13	10	0.74	431	16	0.03	11	220	40	40	<20	103	0.05	<10	85	<10	4	60
34	X09970	2.0	0.80	<5	125	<5	1.57	2	10	111	2831	3.94	<10	0.53	492	13	0.02	5	600	36	15	<20	90	0.06	<10	47	<10	5	45
35	X09971	1.9	0.71	10	85	<5	2.73	12	10	87	1539	2.96	10	0.38	776	11	0.01	4	900	192	10	<20	116	0.05	<10	22	<10	6	420
QC DATA:																													
Repeat:																													
1	X09937	2.6	0.89	10	170	<5	3.21	<1	9	73	1412	2.19	<10	0.56	1248	38	<0.01	3	990	30	10	<20	246	0.01	<10	14	<10	7	69
10	X09946	3.1	0.85	20	65	<5	1.38	2	10	114	1383	4.13	10	0.55	608	13	<0.01	6	1030	46	20	<20	76	0.02	<10	16	<10	3	45
19	X09955	4.3	0.62	<5	60	<5	2.78	<1	12	113	5033	3.51	<10	0.33	773	11	0.01	5	560	58	10	<20	177	0.01	<10	14	<10	6	49
Resplit:																													
1	X09937	2.4	0.98	10	140	<5	3.17	2	9	65	1344	2.52	10	0.63	1254	39	<0.01	5	1050	30	15	<20	238	0.02	<10	15	<10	6	74
Standard:																													
Pb113A		11.6	0.30	55	80	<5	1.74	43	2	6	2437	1.08	<10	0.12	1481	59	0.02	3	70	5754	30	<20	79	0.01	<10	8	<10	<1	6948

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl/nl
dl/5662
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5663

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

22-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07165
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X09972	0.30	0.009
2	X09973	0.56	0.016
3	X09974	0.58	0.017
4	X09975	0.83	0.024
5	X09976	1.49	0.043
6	X09977	0.51	0.015
7	X09978	2.22	0.065
8	X09979	0.47	0.014
9	X09980	0.39	0.011
10	X09981	0.26	0.008
11	X09982	0.33	0.010
12	X09983	0.35	0.010
13	X09984	0.07	0.002
14	X09985	<0.03	<0.001
15	X09986	<0.03	<0.001
16	X09987	<0.03	<0.001
17	X09988	<0.03	<0.001
18	X09989	0.42	0.012
19	X09990	0.72	0.021
20	X09991	1.02	0.030
21	X09992	0.21	0.006
22	X09993	0.51	0.015
23	X09994	0.48	0.014
24	X09995	0.46	0.013
25	X09996	0.37	0.011
26	X09997	0.46	0.013
27	X09998	0.35	0.010
28	X09999	0.27	0.008
29	X10000	4.70	0.137

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5663 22-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X10001	0.35	0.010
31	X10002	1.13	0.033
32	X10003	0.36	0.010
33	X10004	0.27	0.008
34	X10005	0.28	0.008
35	X10006	0.29	0.008
QC DATA:			
Repeat:			
1	X09972	0.31	0.009
7	X09978	1.99	0.058
10	X09981	0.25	0.007
18	X09989	0.38	0.011
19	X09990	0.71	0.021
29	X10000	4.55	0.133
Resplits:			
1	X09972	0.34	0.010
Standard:			
OXi54		1.86	0.054

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

22-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5663

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07165
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X09972	1.1	0.85	10	120	<5	2.08	1	8	107	1190	2.77	10	0.53	579	13	0.03	4	860	26	15	<20	177	0.07	<10	35	<10	5	43
2	X09973	1.1	0.84	<5	70	<5	2.16	1	11	108	1743	3.58	10	0.59	478	14	0.03	6	860	28	15	<20	209	0.07	<10	37	<10	6	43
3	X09974	1.2	0.82	<5	130	<5	2.16	<1	9	79	2119	2.77	<10	0.48	509	16	0.02	3	780	36	<5	<20	154	0.07	<10	26	<10	7	38
4	X09975	2.0	0.87	5	95	<5	1.37	1	10	157	3170	3.35	10	0.57	439	15	0.03	6	680	32	10	<20	120	0.07	<10	33	<10	5	45
5	X09976	2.0	0.80	<5	125	<5	1.63	2	11	89	2776	3.63	10	0.46	465	12	0.02	5	690	34	15	<20	122	0.07	<10	49	<10	5	48
6	X09977	1.4	0.88	15	155	<5	1.37	<1	10	102	1906	2.81	10	0.53	479	22	0.02	4	840	30	10	<20	135	0.09	<10	31	<10	7	62
7	X09978	5.3	0.95	<5	80	<5	1.18	2	12	140	7449	4.03	10	0.61	485	18	0.03	6	230	28	15	<20	67	0.06	<10	40	<10	4	62
8	X09979	1.6	1.01	<5	175	<5	1.71	2	10	112	2340	3.56	10	0.74	608	30	0.03	7	780	26	25	<20	59	0.06	<10	43	<10	6	59
9	X09980	1.2	1.03	5	150	<5	1.03	1	9	173	1471	3.72	10	0.65	528	17	0.03	7	810	30	15	<20	52	0.07	<10	42	<10	6	60
10	X09981	0.8	0.97	10	145	<5	2.11	<1	7	95	1178	2.91	10	0.66	622	14	0.02	4	980	32	10	<20	67	0.06	<10	28	<10	6	53
11	X09982	1.2	1.08	<5	105	<5	1.10	<1	10	157	1551	4.23	10	0.75	565	12	0.03	6	800	32	10	<20	71	0.07	<10	50	<10	4	64
12	X09983	1.2	1.27	5	140	<5	1.33	<1	10	94	1594	3.91	10	0.99	657	16	0.03	7	940	30	5	<20	76	0.10	<10	46	<10	5	79
13	X09984	0.3	2.11	15	60	<5	2.70	<1	19	173	432	3.00	<10	1.86	754	42	0.03	37	790	46	15	<20	318	0.19	<10	61	<10	7	70
14	X09985	<0.2	3.21	30	120	35	3.28	2	36	155	69	3.94	10	4.10	922	7	0.02	76	630	66	40	<20	149	0.24	<10	100	<10	8	59
15	X09986	<0.2	1.20	15	295	25	0.64	<1	7	96	5	2.20	10	0.67	563	1	0.12	5	970	30	5	<20	113	0.17	<10	50	<10	6	42
16	X09987	<0.2	3.23	35	145	35	2.15	<1	38	132	66	3.92	10	4.02	838	4	0.03	75	710	68	30	<20	163	0.28	<10	101	<10	10	49
17	X09988	<0.2	4.08	35	135	55	1.62	1	42	199	75	5.01	10	5.54	1151	10	0.03	108	510	86	50	<20	125	0.22	<10	119	<10	10	54
18	X09989	1.4	1.27	10	185	<5	1.80	1	10	105	2216	3.49	10	0.94	634	14	0.04	7	650	32	15	<20	145	0.10	<10	48	<10	3	72
19	X09990	1.8	1.23	15	90	<5	1.71	1	16	87	1902	4.25	10	0.92	735	22	0.02	5	850	44	10	<20	85	0.07	<10	40	<10	4	84
20	X09991	3.7	1.19	60	65	<5	0.74	4	17	59	3364	3.92	20	0.54	272	219	0.03	14	400	140	40	<20	33	0.04	<10	46	<10	7	156
21	X09992	1.3	1.02	10	75	<5	1.79	2	14	94	1424	3.61	10	0.70	610	21	0.03	6	870	38	20	<20	67	0.07	<10	34	<10	4	68
22	X09993	1.9	1.04	10	90	<5	1.85	2	12	94	2620	3.47	10	0.74	655	26	0.03	5	840	40	15	<20	83	0.08	<10	34	<10	7	75
23	X09994	1.2	1.03	15	150	<5	1.47	1	7	130	1730	2.96	<10	0.65	621	31	0.03	5	770	26	15	<20	64	0.06	<10	33	<10	5	64
24	X09995	1.3	0.95	20	185	<5	1.56	<1	8	127	1902	2.86	<10	0.65	661	29	0.03	4	830	32	10	<20	69	0.07	<10	34	<10	7	62
25	X09996	1.4	0.73	5	100	<5	1.28	<1	10	146	2113	2.54	<10	0.42	454	26	0.02	4	570	34	10	<20	54	0.05	<10	24	<10	5	38

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X09997	1.2	0.89	10	225	<5	1.67	<1	7	88	1633	2.62	10	0.55	628	19	0.02	4	750	30	10	<20	69	0.07	<10	27	<10	6	49
27	X09998	1.4	0.96	10	145	<5	1.93	<1	8	107	1615	3.21	10	0.59	719	50	0.02	4	750	48	10	<20	83	0.07	<10	32	<10	6	63
28	X09999	1.7	0.87	15	165	<5	2.80	1	8	87	1438	2.54	<10	0.52	855	23	0.01	3	790	34	10	<20	117	0.06	<10	21	<10	6	51
29	X10000	4.6	1.01	15	80	<5	2.62	3	11	68	1000	2.91	10	0.62	962	27	<0.01	6	1080	54	25	<20	103	0.06	<10	19	<10	8	81
30	X10001	1.4	0.87	15	170	<5	2.33	<1	9	85	1553	2.45	10	0.53	691	32	0.02	4	860	32	10	<20	130	0.06	<10	22	<10	6	44
31	X10002	2.4	0.86	20	85	<5	2.05	1	10	104	3073	3.19	10	0.50	622	26	0.01	5	640	36	10	<20	104	0.06	<10	25	<10	6	42
32	X10003	1.7	1.00	15	125	<5	1.69	<1	11	92	1693	3.18	10	0.64	752	39	0.02	4	810	38	10	<20	105	0.07	<10	28	<10	6	76
33	X10004	1.0	1.07	10	235	<5	2.84	<1	8	86	1067	3.27	10	0.69	908	37	0.03	4	920	48	10	<20	185	0.08	<10	36	<10	8	76
34	X10005	1.5	0.94	<5	210	<5	0.98	2	12	97	1403	3.59	10	0.59	530	43	0.03	5	840	56	10	<20	84	0.07	<10	41	<10	5	91
35	X10006	3.3	1.02	15	70	<5	0.99	9	12	84	1444	2.91	10	0.63	730	68	0.01	4	860	536	10	<20	59	0.07	<10	21	<10	5	769
QC DATA:																													
Repeat:																													
1	X09972	1.2	0.89	15	130	<5	2.12	1	9	112	1208	2.81	10	0.54	587	14	0.03	4	890	30	10	<20	178	0.08	<10	36	<10	7	44
10	X09981	0.8	0.99	20	150	<5	2.10	1	7	97	1146	2.87	10	0.65	615	15	0.02	5	980	36	10	<20	80	0.06	<10	29	<10	7	52
19	X09990	1.3	1.28	10	100	<5	1.75	1	16	90	1954	4.29	10	0.94	739	24	0.03	5	830	44	15	<20	87	0.08	<10	41	<10	4	83
Resplit:																													
1	X09972	1.0	0.92	10	130	<5	2.21	1	9	117	1190	2.80	10	0.51	591	15	0.04	6	890	28	10	<20	191	0.09	<10	36	<10	6	39
Standard:																													
Pb113A		11.2	0.22	45	65	<5	1.69	31	3	5	2269	1.11	<10	0.12	1511	65	0.02	3	60	5454	15	<20	86	0.01	<10	9	<10	<1	6956

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
dl/5662
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5664

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

22-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07166
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10007	0.28	0.008
2	X10008	0.28	0.008
3	X10009	0.26	0.008
4	X10010	0.32	0.009
5	X10011	0.27	0.008
6	X10012	0.21	0.006
7	X10013	0.18	0.005
8	X10014	0.13	0.004
9	X10015	0.31	0.009
10	X10016	0.16	0.005
11	X10017	0.21	0.006
12	X10018	0.22	0.006
13	X10019	0.28	0.008
14	X10020	0.29	0.008
15	X10021	0.20	0.006
16	X10022	0.26	0.008
17	X10023	0.34	0.010
18	X10024	0.48	0.014
19	X10025	1.88	0.055
20	X10026	0.48	0.014
21	X10027	0.47	0.014
22	X10028	0.28	0.008
23	X10029	0.36	0.010
24	X10030	0.47	0.014
25	X10031	0.53	0.015
26	X10032	0.72	0.021
27	X10033	0.48	0.014
28	X10034	0.39	0.011
29	X10035	0.26	0.008

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5664 22-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X10036	<0.03	<0.001
31	X10037	0.34	0.010
32	X10038	0.22	0.006
33	X10039	1.85	0.054
34	X10040	1.24	0.036
35	X10041	0.31	0.009

QC DATA:

Repeat:

1	X10007	0.30	0.009
10	X10016	0.12	0.003
19	X10025	2.01	0.059

Resplits:

1	X10007	0.35	0.010

Standard:

OXK48		3.58	0.104

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

23-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5664

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07166
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10007	3.8	0.53	20	45	<5	1.57	10	11	184	1370	3.86	<10	0.21	725	48	<0.01	4	1060	198	<5	<20	69	0.07	<10	9	<10	7	349
2	X10008	1.4	0.60	10	135	<5	2.48	2	8	152	1337	2.11	<10	0.26	790	36	<0.01	4	860	62	<5	<20	124	0.07	<10	10	<10	7	78
3	X10009	1.1	0.70	15	75	<5	4.65	2	10	127	1168	2.30	<10	0.39	1401	23	<0.01	5	1140	34	<5	<20	165	0.08	<10	11	<10	10	49
4	X10010	1.1	0.86	10	265	<5	2.57	2	9	108	1217	2.96	<10	0.48	898	62	0.02	4	1280	14	<5	<20	138	0.09	<10	25	<10	9	57
5	X10011	0.9	0.84	10	250	<5	1.85	2	11	112	1136	3.68	<10	0.48	703	41	0.02	4	1300	14	<5	<20	232	0.09	<10	32	<10	9	55
6	X10012	0.7	0.78	10	650	<5	2.36	2	9	114	815	3.33	<10	0.44	757	63	0.02	4	1340	12	<5	<20	561	0.09	<10	36	<10	8	57
7	X10013	0.6	0.79	10	450	<5	2.63	2	10	117	852	2.92	<10	0.44	838	40	0.02	4	1250	18	<5	<20	256	0.09	<10	33	<10	8	69
8	X10014	1.0	0.86	10	565	<5	2.15	2	11	83	604	3.37	<10	0.50	845	46	0.02	3	1370	22	<5	<20	484	0.10	<10	38	<10	8	73
9	X10015	1.3	0.89	10	440	<5	1.64	3	12	152	1477	3.73	<10	0.53	753	34	0.02	4	1270	18	<5	<20	314	0.10	<10	42	<10	8	76
10	X10016	0.5	0.89	10	570	<5	1.99	2	10	86	560	3.84	<10	0.53	818	54	0.02	4	1410	10	<5	<20	167	0.11	<10	45	<10	9	82
11	X10017	0.5	0.98	10	705	<5	2.63	2	11	115	893	3.80	<10	0.60	968	69	0.02	4	1420	10	<5	<20	213	0.12	<10	43	<10	9	91
12	X10018	1.3	0.78	20	135	<5	2.40	2	10	120	1235	3.10	<10	0.41	898	76	0.02	4	1290	76	<5	<20	128	0.09	<10	24	<10	9	81
13	X10019	1.2	0.93	20	145	<5	1.97	10	11	111	1034	2.84	<10	0.52	940	46	0.01	4	1370	50	<5	<20	102	0.09	<10	19	<10	9	270
14	X10020	1.5	0.92	15	205	<5	2.09	3	11	119	1545	2.70	<10	0.50	899	137	0.01	5	1460	16	<5	<20	117	0.11	<10	21	<10	11	125
15	X10021	3.4	0.79	15	90	<5	2.54	2	13	122	1129	3.17	<10	0.36	895	176	0.01	4	1480	92	<5	<20	144	0.10	<10	18	<10	10	81
16	X10022	2.2	0.81	15	95	<5	2.40	2	12	135	1406	2.92	<10	0.42	984	73	0.01	4	1110	22	<5	<20	174	0.09	<10	12	<10	7	110
17	X10023	1.8	0.78	15	120	<5	1.88	2	9	150	1311	2.97	<10	0.40	797	102	0.01	4	1170	28	<5	<20	123	0.11	<10	16	<10	8	99
18	X10024	1.7	0.84	15	125	<5	1.45	1	9	155	1388	2.60	<10	0.48	690	105	0.01	4	1030	22	<5	<20	99	0.08	<10	14	<10	7	76
19	X10025	3.0	0.95	20	60	<5	1.55	4	14	152	2446	4.39	<10	0.56	768	59	0.01	4	1150	56	<5	<20	106	0.10	<10	19	<10	8	141
20	X10026	1.7	0.83	25	65	<5	1.94	5	12	140	1110	3.05	<10	0.41	962	123	<0.01	4	1280	138	<5	<20	150	0.10	<10	15	<10	9	140
21	X10027	2.1	0.93	20	130	<5	2.87	2	11	136	1723	3.58	<10	0.52	1190	411	0.01	4	1120	24	<5	<20	170	0.10	<10	27	<10	10	105
22	X10028	1.3	0.82	10	200	<5	1.78	2	12	134	1113	3.74	<10	0.44	884	145	0.02	4	1320	10	<5	<20	139	0.11	<10	34	<10	9	82
23	X10029	1.1	0.82	10	340	<5	1.97	2	11	107	1147	3.33	<10	0.44	856	137	0.02	4	1330	14	<5	<20	184	0.10	<10	32	<10	8	83
24	X10030	1.4	0.92	10	280	<5	2.34	3	13	115	1387	3.73	<10	0.59	982	276	0.02	4	1260	198	<5	<20	223	0.11	<10	40	<10	9	124
25	X10031	2.4	0.92	25	120	<5	2.86	2	14	126	1440	3.90	<10	0.52	1234	79	0.01	4	1270	38	<5	<20	172	0.10	<10	27	<10	9	109

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10032	3.2	0.61	25	85	<5	2.11	5	11	174	2103	2.36	<10	0.30	806	611	<0.01	5	1050	54	<5	<20	109	0.10	<10	12	<10	8	120
27	X10033	2.3	0.65	15	115	<5	1.10	2	9	166	1566	1.76	<10	0.34	543	411	<0.01	5	1040	798	<5	<20	57	0.09	<10	11	<10	8	70
28	X10034	2.1	0.76	15	110	<5	2.49	2	10	133	1608	2.70	<10	0.44	923	116	0.01	4	1170	98	<5	<20	153	0.12	<10	20	<10	10	70
29	X10035	1.8	0.80	15	85	<5	2.20	3	12	144	1161	3.54	<10	0.44	868	243	0.01	4	1230	30	<5	<20	144	0.12	<10	23	<10	9	103
30	X10036	<0.2	1.10	10	305	<5	0.66	1	10	145	3	2.26	<10	0.53	700	1	0.06	8	900	<2	<5	<20	109	0.21	<10	46	<10	6	56
31	X10037	2.0	0.78	15	95	<5	2.72	2	12	115	1142	2.98	<10	0.43	1119	145	0.01	4	1250	36	<5	<20	134	0.10	<10	15	<10	9	91
32	X10038	1.5	0.89	15	145	<5	2.55	2	14	129	946	3.18	<10	0.48	1036	42	0.01	4	1350	10	<5	<20	187	0.11	<10	21	<10	8	75
33	X10039	3.8	1.26	45	65	<5	1.14	5	28	69	8720	4.79	20	0.56	245	708	0.03	94	810	78	25	<20	71	0.07	<10	42	<10	9	101
34	X10040	4.1	0.81	15	95	<5	1.76	4	13	110	3078	2.75	<10	0.46	722	444	0.01	5	1180	58	<5	<20	119	0.12	<10	15	<10	8	140
35	X10041	1.5	0.83	15	140	<5	2.20	2	12	149	1137	3.14	<10	0.43	899	117	0.01	4	1200	12	<5	<20	164	0.10	<10	19	<10	7	72
QC DATA:																													
Repeat:																													
1	X10007	3.8	0.50	20	50	<5	1.62	10	11	181	1381	3.92	<10	0.21	730	51	<0.01	4	1060	192	<5	<20	71	0.06	<10	8	<10	7	345
10	X10016	0.6	0.88	10	525	<5	2.02	2	10	86	531	3.83	<10	0.51	841	55	0.02	3	1420	8	<5	<20	162	0.11	<10	43	<10	9	84
19	X10025	3.0	0.91	20	55	<5	1.60	4	15	153	2401	4.49	<10	0.56	810		0.01	4	1160	62	<5	<20	109	0.09	<10	18	<10	8	151
Resplit:																													
1	X10007	3.9	0.50	15	65	<5	1.69	5	12	185	1415	3.39	<10	0.23	819	44	<0.01	5	1070	198	<5	<20	73	0.08	<10	9	<10	8	343
Standard:																													
Pb113A		11.6	0.28	70	85	<5	1.77	72	3	<1	2374	1.39	<10	0.09	1793	80	<0.01	1	100	5614	10	<20	107	0.02	<10	7	<10	1	7113

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
dl/N5664s
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5666

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

22-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 070-167
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10042	0.20	0.006
2	X10043	0.16	0.005
3	X10044	0.31	0.009
4	X10045	0.33	0.010
5	X10046	0.64	0.019
6	X10047	0.22	0.006
7	X10048	0.24	0.007
8	X10049	0.15	0.004
9	X10050	0.19	0.006
10	X10051	0.45	0.013
11	X10052	0.38	0.011
12	X10053	0.20	0.006
13	X10054	0.23	0.007
14	X10055	0.12	0.003
15	X10056	0.20	0.006
16	X10057	0.42	0.012
17	X10058	0.23	0.007
18	X10059	0.23	0.007
19	X10060	0.38	0.011
20	X10061	0.23	0.007
21	X10062	0.15	0.004
22	X10063	0.13	0.004
23	X10064	0.31	0.009
24	X10065	0.35	0.010
25	X10066	0.28	0.008
26	X10067	0.45	0.013
27	X10068	0.37	0.011
28	X10069	<0.03	<0.001
29	X10070	0.36	0.010

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5666 22-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X10071	0.27	0.008
31	X10072	0.18	0.005
32	X10073	0.25	0.007
33	X10074	0.22	<0.001
34	X10075	0.15	0.004
35	X10076	0.19	0.006

QC DATA:

Repeat:

1	X10042	0.21	0.006
10	X10051	0.42	0.012

Resplits:

1	X10042	0.21	0.006

Standard:

OXK48		3.52	0.103

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

26-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5666

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07-167
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10042	1.5	0.72	<5	75	<5	1.58	1	10	90	1253	2.31	<10	0.44	571	87	0.02	4	640	26	10	<20	123	0.05	<10	21	<10	5	48
2	X10043	0.8	0.80	10	65	<5	1.88	<1	11	70	599	2.72	10	0.51	618	92	0.03	4	810	48	5	<20	157	0.06	<10	26	<10	8	58
3	X10044	1.6	0.68	10	65	<5	1.02	<1	9	85	1051	2.48	<10	0.41	465	95	0.02	3	820	38	10	<20	67	0.05	<10	18	<10	7	62
4	X10045	1.8	0.81	10	75	<5	1.11	<1	10	100	1402	2.18	<10	0.55	607	105	0.02	4	760	32	5	<20	64	0.04	<10	22	<10	7	89
5	X10046	4.9	0.64	5	50	<5	1.29	<1	11	102	2786	2.59	<10	0.38	561	215	0.01	5	560	30	10	<20	56	0.03	<10	21	<10	6	57
6	X10047	2.3	0.40	<5	55	<5	1.82	<1	7	113	740	1.90	<10	0.19	556	242	0.01	3	470	28	5	<20	59	0.03	<10	10	<10	6	28
7	X10048	2.3	0.75	5	100	<5	2.62	1	8	100	975	1.92	<10	0.48	880	67	0.01	4	730	32	10	<20	154	0.05	<10	15	<10	8	92
8	X10049	1.4	0.71	10	90	<5	2.30	<1	9	94	1003	1.92	<10	0.44	635	62	0.02	4	750	36	<5	<20	109	0.05	<10	18	<10	8	65
9	X10050	1.0	0.75	10	110	<5	2.51	<1	7	77	894	1.85	<10	0.49	679	164	0.02	3	780	32	5	<20	133	0.04	<10	15	<10	9	57
10	X10051	1.9	0.68	20	100	<5	2.57	<1	8	92	1517	1.67	<10	0.43	617	129	0.03	3	680	30	5	<20	216	0.05	<10	17	<10	9	45
11	X10052	1.8	0.81	<5	55	<5	2.21	2	18	72	1530	2.97	10	0.56	624	64	0.03	6	770	30	25	<20	131	0.04	<10	25	<10	7	63
12	X10053	1.3	0.74	10	145	<5	1.65	<1	8	74	903	1.96	<10	0.50	499	78	0.03	3	900	32	5	<20	109	0.06	<10	25	<10	10	46
13	X10054	1.5	0.74	10	70	<5	1.90	<1	10	104	783	2.22	<10	0.51	656	80	0.02	4	900	48	5	<20	87	0.05	<10	20	<10	9	77
14	X10055	0.9	0.70	<5	100	<5	1.98	<1	7	81	653	1.43	<10	0.55	533	56	0.05	4	910	32	5	<20	160	0.05	<10	24	<10	9	44
15	X10056	1.1	0.67	10	135	<5	1.74	<1	7	87	890	1.31	<10	0.51	510	102	0.03	3	740	40	5	<20	92	0.04	<10	18	<10	9	40
16	X10057	2.5	0.70	25	65	<5	2.65	2	10	93	961	2.55	<10	0.44	974	101	0.01	4	760	46	10	<20	71	0.05	<10	16	<10	9	92
17	X10058	3.3	0.57	15	65	<5	2.75	4	8	103	947	2.18	<10	0.31	838	66	0.01	4	770	54	<5	<20	103	0.04	<10	14	<10	9	165
18	X10059	1.4	0.84	5	75	<5	1.98	1	14	71	995	2.54	<10	0.60	616	53	0.03	4	890	38	10	<20	85	0.05	<10	24	<10	10	78
19	X10060	2.6	0.79	20	60	<5	1.96	2	11	78	1291	2.92	<10	0.52	699	78	0.01	4	860	36	<5	<20	58	0.04	<10	19	<10	8	69
20	X10061	1.7	0.68	10	70	<5	1.95	<1	10	73	1080	2.06	<10	0.43	498	320	0.02	4	690	26	5	<20	74	0.04	<10	20	<10	7	73
21	X10062	0.7	0.77	5	130	<5	2.94	<1	9	94	583	2.50	<10	0.49	605	39	0.03	4	840	32	5	<20	188	0.06	<10	34	<10	8	48
22	X10063	0.6	0.83	5	155	<5	1.95	1	10	85	584	2.71	10	0.57	521	57	0.04	5	890	22	15	<20	157	0.06	<10	40	<10	7	51
23	X10064	1.1	0.91	<5	90	<5	2.04	<1	10	78	640	2.90	<10	0.65	571	46	0.04	4	880	30	<5	<20	168	0.06	<10	35	<10	8	47
24	X10065	1.5	1.05	5	105	<5	2.81	<1	12	76	835	2.69	<10	0.88	756	91	0.04	4	1340	40	10	<20	112	0.06	<10	46	<10	9	71
25	X10066	2.9	0.92	15	70	<5	3.69	1	13	78	1899	2.96	10	0.66	1048	92	0.02	4	1120	46	10	<20	96	0.05	<10	28	<10	10	91

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10067	2.3	0.93	<5	60	<5	2.37	1	13	86	1814	3.58	10	0.69	656	106	0.03	5	940	42	5	<20	105	0.05	<10	50	<10	8	58
27	X10068	1.8	1.34	15	80	<5	1.85	1	14	99	1493	4.82	10	1.16	819	63	0.04	6	1250	44	10	<20	73	0.06	<10	69	<10	7	116
28	X10069	<0.2	1.06	<5	265	15	0.57	<1	6	88	8	2.25	<10	0.62	542	2	0.10	6	960	20	<5	<20	97	0.13	<10	48	<10	5	44
29	X10070	1.8	1.10	5	85	<5	2.55	1	13	97	1309	3.56	10	0.90	783	40	0.05	6	1280	38	10	<20	113	0.06	<10	79	<10	7	92
30	X10071	3.1	1.22	35	50	<5	0.99	3	21	59	2639	3.66	20	0.63	199	197	0.03	10	420	58	15	<20	65	0.04	<10	46	<10	10	280
31	X10072	0.9	1.19	<5	145	<5	2.83	<1	14	67	676	3.99	10	1.00	835	94	0.05	4	1410	40	10	<20	126	0.07	<10	84	<10	8	94
32	X10073	1.0	1.15	15	100	<5	1.98	<1	11	75	976	2.82	10	1.08	608	365	0.05	4	1260	40	15	<20	88	0.07	<10	67	<10	10	96
33	X10074	1.3	1.10	20	105	<5	1.95	3	11	93	866	2.77	10	1.02	592	590	0.05	6	1210	46	20	<20	98	0.06	<10	65	<10	10	164
34	X10075	1.3	1.05	5	70	<5	3.17	1	15	78	702	3.72	10	0.82	781	97	0.03	5	1340	44	5	<20	101	0.06	<10	54	<10	8	110
35	X10076	0.9	1.15	10	65	<5	2.35	1	15	50	762	3.70	10	0.98	622	58	0.04	5	1450	40	15	<20	134	0.07	<10	61	<10	7	68
QC DATA:																													
Repeat:																													
1	X10042	1.5	0.76	5	85	<5	1.65	<1	10	91	1335	2.40	<10	0.48	598	96	0.03	4	690	30	10	<20	136	0.05	<10	22	<10	7	50
10	X10051	1.7	0.65	10	100	<5	2.53	<1	8	90	1444	1.65	<10	0.41	605	129	0.02	4	670	30	5	<20	206	0.05	<10	16	<10	9	45
19	X10060	2.7	0.76	15	70	<5	1.94	1	11	76	1276	2.92	<10	0.51	694	78	0.01	4	870	36	5	<20	59	0.04	<10	19	<10	9	69
Resplit:																													
1	X10042	1.5	0.75	<5	85	<5	1.70	<1	11	104	1265	2.45	<10	0.46	612	78	0.02	4	720	30	10	<20	126	0.05	<10	21	<10	7	50
Standard:																													
Pb113A		11.8	0.26	60	65	<5	1.64	38	3	4	2244	1.08	<10	0.10	1487	56	0.02	2	70	5526	10	<20	77	0.01	<10	7	<10	<1	6945

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
dl/5666S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5667

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

22-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07168
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05343	0.49	0.014
2	X05344	0.56	0.016
3	X05345	0.56	0.016
4	X05346	0.38	0.011
5	X05347	0.21	0.006
6	X05348	0.38	0.011
7	X05349	0.22	0.006
8	X05350	<0.03	<0.001
9	X05351	0.14	0.004
10	X05352	0.15	0.004
11	X05353	0.06	0.002
12	X05354	0.04	0.001
13	X05355	0.05	0.001
14	X05356	0.07	0.002
15	X05357	0.08	0.002
16	X05358	0.10	0.003
17	X05359	0.22	0.006
18	X05360	0.39	0.011
19	X05361	0.52	0.015
20	X05362	0.14	0.004
21	X05363	0.09	0.003
22	X05364	0.24	0.007
23	X05365	0.27	0.008
24	X05366	0.23	0.007
25	X05367	0.24	0.007
26	X05368	0.21	0.006
27	X05369	0.06	0.002
28	X05370	0.41	0.012
29	X05371	0.20	0.006

Lydia Bosa /pes
ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5667 22-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X05372	0.31	0.009
31	X05373	0.23	0.007
32	X05374	0.89	0.026
33	X05375	1.02	0.030
34	X05376	0.80	0.023
35	X05377	0.78	0.023

QC DATA:

Repeat:

1	X05343	0.58	0.017
10	X05352	0.20	0.006
19	X05361	0.47	0.014

Resplits:

1	X05343	0.60	0.017

Standard:

OXK48		3.50	0.102

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

26-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5667

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07168
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05343	1.2	1.13	<5	50	10	0.33	1	18	78	387	6.33	<10	0.63	245	60	0.03	17	1120	44	<5	<20	32	0.05	<10	16	<10	<1	40
2	X05344	0.5	1.55	<5	50	15	0.24	<1	17	60	379	5.02	<10	1.07	343	47	0.03	20	910	40	<5	<20	31	0.04	<10	19	<10	<1	54
3	X05345	0.7	1.71	<5	50	<5	0.22	<1	20	95	454	5.64	<10	1.20	379	60	0.03	21	900	44	<5	<20	26	0.05	<10	21	<10	<1	60
4	X05346	0.3	0.99	<5	45	<5	0.18	<1	18	103	391	5.94	<10	0.59	203	25	0.03	19	710	36	<5	<20	31	0.04	<10	12	<10	<1	34
5	X05347	0.5	0.69	<5	45	<5	0.15	<1	15	117	358	4.06	<10	0.34	119	28	0.03	19	590	26	<5	<20	33	0.03	<10	8	<10	<1	25
6	X05348	0.3	1.30	10	50	<5	0.26	<1	23	75	469	4.86	<10	0.89	236	31	0.03	26	1060	34	<5	<20	34	0.04	<10	22	<10	3	54
7	X05349	0.4	1.02	<5	45	<5	0.24	<1	20	82	386	4.73	<10	0.63	165	72	0.03	23	950	34	<5	<20	28	0.04	<10	13	<10	<1	37
8	X05350	<0.2	0.94	<5	255	30	0.70	<1	7	101	6	2.02	<10	0.68	502	1	0.10	6	800	24	5	<20	97	0.13	<10	43	<10	2	41
9	X05351	0.3	0.71	<5	55	<5	0.16	<1	13	93	207	3.41	<10	0.32	86	31	0.04	16	610	34	<5	<20	20	0.03	<10	8	<10	<1	21
10	X05352	0.4	0.65	<5	45	<5	0.16	<1	13	97	332	3.50	<10	0.31	87	61	0.03	17	630	34	<5	<20	25	0.03	<10	7	<10	<1	21
11	X05353	0.3	0.35	<5	45	10	0.09	<1	10	130	113	3.44	<10	0.07	40	154	0.03	11	320	24	<5	<20	25	0.03	<10	3	<10	<1	7
12	X05354	0.2	0.34	<5	45	20	0.10	<1	9	122	55	2.86	<10	0.09	47	96	0.03	8	350	24	<5	<20	24	0.02	<10	3	<10	<1	7
13	X05355	0.2	0.41	<5	50	5	0.10	<1	10	129	178	3.62	<10	0.09	60	93	0.03	9	320	20	<5	<20	23	0.03	<10	3	<10	<1	8
14	X05356	0.2	0.54	<5	40	15	0.19	<1	12	140	171	4.13	<10	0.23	135	126	0.03	11	350	22	<5	<20	21	0.03	<10	5	<10	<1	19
15	X05357	0.3	0.46	<5	40	<5	0.29	<1	13	111	300	3.81	<10	0.16	113	25	0.03	15	460	28	<5	<20	34	0.03	<10	4	<10	<1	14
16	X05358	1.0	0.57	35	40	<5	0.32	3	15	114	374	4.59	<10	0.27	135	71	0.03	19	620	46	5	<20	30	0.03	<10	6	<10	<1	67
17	X05359	0.4	0.51	<5	40	<5	0.20	<1	14	85	252	3.89	<10	0.24	98	46	0.03	17	530	42	<5	<20	25	0.03	<10	5	<10	<1	36
18	X05360	1.1	1.19	<5	125	<5	1.63	<1	14	23	4064	3.33	<10	1.10	688	4	0.18	11	1170	34	<5	<20	109	0.18	<10	169	<10	5	43
19	X05361	0.6	0.60	10	45	<5	0.29	<1	18	120	157	3.79	<10	0.33	144	46	0.03	15	470	32	<5	<20	31	0.03	<10	5	<10	<1	40
20	X05362	0.5	0.76	15	45	10	0.26	1	13	97	163	3.89	<10	0.47	148	21	0.03	17	680	82	<5	<20	32	0.03	<10	8	<10	<1	47
21	X05363	0.4	0.64	10	40	10	0.21	<1	11	102	285	3.92	<10	0.36	126	51	0.03	14	520	66	<5	<20	23	0.03	<10	7	<10	<1	32
22	X05364	0.5	1.07	10	45	10	0.48	2	20	90	272	5.61	<10	0.77	261	211	0.03	25	1260	86	5	<20	37	0.04	<10	20	<10	1	129
23	X05365	0.2	1.29	<5	50	<5	0.54	3	20	77	317	4.76	<10	1.03	304	113	0.03	13	1780	44	<5	<20	26	0.04	<10	27	<10	3	182
24	X05366	0.2	0.94	<5	45	<5	0.51	<1	22	72	283	4.11	<10	0.67	222	49	0.03	23	1590	28	<5	<20	26	0.03	<10	15	<10	3	31
25	X05367	0.3	1.05	<5	50	<5	0.46	<1	27	62	409	5.99	<10	0.80	251	65	0.03	7	1430	30	<5	<20	18	0.04	<10	17	<10	<1	35

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05368	0.9	0.70	30	45	<5	0.62	3	26	95	534	5.71	<10	0.46	246	101	0.03	16	950	42	10	<20	27	0.04	<10	12	<10	<1	47
27	X05369	0.5	0.46	10	40	10	0.19	1	13	85	169	3.44	<10	0.23	78	27	0.02	13	500	44	<5	<20	31	0.03	<10	4	<10	<1	21
28	X05370	0.6	1.39	<5	35	<5	0.35	<1	21	61	390	4.41	<10	1.14	263	129	0.03	26	1370	34	<5	<20	16	0.03	<10	23	<10	2	53
29	X05371	0.7	0.90	10	35	<5	0.42	2	14	92	313	4.34	<10	0.65	199	96	0.03	13	930	62	10	<20	60	0.03	<10	11	<10	<1	39
30	X05372	0.8	0.95	15	40	<5	0.36	3	22	81	612	5.05	<10	0.67	167	56	0.03	21	1090	64	5	<20	31	0.04	<10	12	<10	<1	46
31	X05373	0.6	1.09	5	45	<5	1.10	2	19	95	459	4.64	<10	0.79	402	127	0.03	7	1440	44	<5	<20	48	0.04	<10	17	<10	5	38
32	X05374	0.2	1.94	10	50	<5	0.21	1	13	82	1646	4.77	<10	1.46	542	69	0.01	3	910	58	10	<20	22	0.04	<10	25	<10	2	213
33	X05375	1.6	1.63	<5	50	<5	0.21	2	12	108	1869	3.98	<10	1.10	507	140	0.01	4	860	44	<5	<20	13	0.03	<10	21	<10	<1	336
34	X05376	1.8	0.81	<5	45	<5	0.21	1	13	111	1578	4.85	<10	0.44	234	152	0.01	4	940	80	<5	<20	30	0.04	<10	12	<10	1	209
35	X05377	1.8	1.67	<5	40	<5	0.25	1	15	84	1602	4.95	<10	1.11	581	77	0.01	3	1010	102	<5	<20	18	0.05	<10	20	<10	<1	471
QC DATA:																													
Repeat:																													
1	X05343	0.9	1.11	<5	50	5	0.33	1	18	77	384	6.24	<10	0.62	242	60	0.03	16	1090	46	<5	<20	32	0.05	<10	15	<10	<1	40
10	X05352	0.3	0.61	<5	45	<5	0.16	<1	13	93	344	3.44	<10	0.30	86	61	0.03	17	640	32	<5	<20	24	0.03	<10	7	<10	<1	20
19	X05361	0.5	0.55	10	40	5	0.29	1	18	116	152	3.75	<10	0.31	140	42	0.02	15	460	34	<5	<20	32	0.03	<10	5	<10	<1	39
Resplit:																													
1	X05343	0.9	1.17	<5	40	5	0.35	<1	19	75	376	6.26	<10	0.64	250	66	0.03	18	1160	44	<5	<20	28	0.05	<10	16	<10	<1	37
Standard:																													
PB113A		11.6	0.27	40	55	<5	1.65	39	2	6	2307	1.04	<10	0.11	1497	72	0.02	2	90	5394	15	<20	89	0.03	<10	8	<10	<1	7163

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/
df/
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5668

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

26-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07169
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05378	0.97	0.028
2	X05379	0.76	0.022
3	X05380	0.65	0.019
4	X05381	0.69	0.020
5	X05382	0.41	0.012
6	X05383	0.55	0.016
7	X05384	0.54	0.016
8	X05385	0.60	0.017
9	X05386	0.81	0.024
10	X05387	1.12	0.033
11	X05388	1.13	0.033
12	X05389	1.00	0.029
13	X05390	1.12	0.033
14	X05391	0.91	0.027
15	X05392	0.89	0.026
16	X05393	0.76	0.022
17	X05394	0.94	0.027
18	X05395	0.91	0.027
19	X05396	0.51	0.015
20	X05397	1.19	0.035
21	X05398	1.04	0.030
22	X05399	0.98	0.029
23	X05400	0.94	0.027
24	X05401	0.90	0.026
25	X05402	0.99	0.029
26	X05403	0.57	0.017
27	X05404	1.81	0.053
28	X05405	0.66	0.019
29	X05406	0.58	0.017

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5668 26-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X05407	1.03	0.030
31	X05408	<0.03	<0.001
32	X05409	1.03	0.030
33	X05410	0.74	0.022
34	X05411	0.89	0.026
35	X05412	1.18	0.034

QC DATA:

Repeat:

1	X05378	0.92	0.027
10	X05387	1.03	0.030
19	X05396	0.60	0.017
20	X05397	1.14	0.033
21	X05398	0.95	0.028
35	X05412	1.10	0.032

Resplits:

1	X05378	0.89	0.026

Standard:

OXK48		3.52	0.103

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

27-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5668

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07169
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05378	2.0	0.51	<5	35	<5	0.25	6	13	79	1719	4.65	<10	0.24	184	92	0.01	4	1160	176	<5	<20	5	0.07	<10	9	<10	<1	700
2	X05379	1.8	0.31	<5	30	<5	0.25	2	14	60	1428	4.98	<10	0.03	93	39	0.01	2	1170	138	<5	<20	7	0.07	<10	5	<10	<1	254
3	X05380	1.4	1.26	<5	30	<5	0.25	3	10	52	1664	3.92	<10	0.87	339	32	<0.01	5	1190	40	<5	<20	<1	0.06	<10	21	<10	1	242
4	X05381	1.6	1.10	<5	35	<5	0.26	2	10	102	1960	3.89	<10	0.76	446	25	<0.01	4	770	30	<5	<20	8	0.07	<10	18	<10	<1	195
5	X05382	0.9	1.27	<5	50	<5	0.21	2	8	125	1164	3.66	<10	0.82	404	15	<0.01	6	850	38	<5	<20	6	0.05	<10	17	<10	<1	233
6	X05383	1.1	1.22	<5	35	<5	0.23	<1	7	138	1189	3.18	<10	0.84	438	13	0.01	3	710	224	<5	<20	<1	0.06	<10	16	<10	<1	231
7	X05384	0.9	2.06	<5	60	<5	0.27	1	10	74	1489	4.65	<10	1.54	700	15	<0.01	6	1130	32	10	<20	7	0.08	<10	30	<10	<1	411
8	X05385	1.6	0.36	<5	15	<5	0.17	3	12	137	1425	5.04	<10	0.09	133	131	0.01	4	650	48	<5	<20	18	0.07	<10	7	<10	<1	110
9	X05386	1.5	0.23	<5	30	<5	0.16	3	12	119	1457	4.81	<10	<0.01	92	81	0.01	3	680	100	<5	<20	<1	0.07	<10	6	<10	<1	314
10	X05387	2.8	0.23	165	20	<5	0.15	7	11	130	2103	5.33	<10	<0.01	67	83	0.01	2	570	144	75	<20	5	0.08	<10	5	<10	<1	606
11	X05388	1.9	0.24	<5	35	<5	0.17	9	14	127	2147	6.94	<10	<0.01	90	60	0.01	10	690	176	<5	<20	7	0.08	<10	7	<10	<1	607
12	X05389	1.7	0.25	<5	20	<5	0.16	4	16	142	2099	5.45	<10	<0.01	78	64	0.01	6	680	148	<5	<20	<1	0.08	<10	6	<10	<1	438
13	X05390	1.7	0.20	10	25	<5	0.12	3	13	173	1825	4.80	<10	<0.01	90	479	0.01	6	450	166	<5	<20	2	0.07	<10	6	<10	<1	252
14	X05391	1.4	0.28	<5	30	<5	0.23	2	11	152	1256	4.93	<10	<0.01	126	68	0.01	5	980	108	<5	<20	11	0.08	<10	7	<10	<1	139
15	X05392	1.8	0.31	<5	25	<5	0.21	3	14	128	1477	5.46	<10	0.03	149	77	0.01	6	870	108	<5	<20	6	0.08	<10	7	<10	<1	301
16	X05393	2.2	0.30	30	30	<5	0.29	5	15	151	1809	4.75	<10	0.02	171	71	0.01	6	1060	100	15	<20	56	0.06	<10	8	<10	<1	355
17	X05394	1.8	0.32	40	25	<5	0.28	1	11	170	1588	4.15	<10	0.03	163	77	0.02	4	1190	62	<5	<20	26	0.07	<10	8	<10	<1	134
18	X05395	1.4	0.26	15	15	<5	0.17	3	10	139	1839	4.95	<10	<0.01	76	86	0.01	6	680	56	<5	<20	2	0.08	<10	6	<10	<1	212
19	X05396	0.8	0.30	45	25	<5	0.23	1	9	166	1636	4.40	<10	0.05	138	82	0.01	5	880	52	<5	<20	31	0.07	<10	8	<10	<1	170
20	X05397	1.2	0.29	30	10	<5	0.23	3	8	149	2011	4.93	<10	0.04	125	95	0.01	5	880	48	<5	<20	24	0.07	<10	7	<10	<1	199
21	X05398	1.0	0.30	20	30	<5	0.26	2	10	164	1804	4.53	<10	0.04	130	109	0.01	8	1010	54	<5	<20	88	0.07	<10	8	<10	<1	133
22	X05399	0.8	0.29	25	25	<5	0.24	3	9	149	1958	4.27	<10	0.03	110	93	0.01	7	900	48	<5	<20	35	0.05	<10	7	<10	<1	137
23	X05400	1.0	0.29	25	30	<5	0.28	4	10	160	1896	4.51	<10	0.02	111	87	0.01	6	1120	46	<5	<20	34	0.06	<10	7	<10	<1	334
24	X05401	1.1	0.29	30	30	<5	0.24	1	10	171	1653	3.42	<10	0.03	101	137	0.02	3	920	36	<5	<20	22	0.06	<10	6	<10	<1	121
25	X05402	2.1	0.33	30	25	<5	0.36	5	9	151	1818	4.43	<10	0.02	129	89	0.02	5	1430	118	5	<20	26	0.08	<10	8	<10	<1	485

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05403	1.2	0.31	<5	30	<5	0.26	4	12	149	1464	5.41	<10	0.04	176	57	0.01	7	960	142	<5	<20	39	0.12	<10	7	<10	<1	366
27	X05404	3.9	1.07	25	55	<5	1.01	3	21	59	8499	4.02	<10	0.56	198	645	0.04	63	150	70	20	<20	52	0.10	<10	44	<10	5	76
28	X05405	0.8	0.31	20	30	<5	0.32	2	15	154	1149	5.24	<10	0.06	183	57	0.01	5	1190	98	<5	<20	97	0.08	<10	7	<10	<1	101
29	X05406	1.6	0.33	35	25	<5	0.07	1	12	162	1863	4.99	<10	0.08	130	83	0.01	4	140	80	10	<20	19	0.08	<10	8	<10	<1	167
30	X05407	1.5	0.24	<5	25	<5	0.13	2	7	158	1684	4.93	<10	<0.01	67	105	0.02	9	300	88	<5	<20	16	0.08	<10	6	<10	<1	249
31	X05408	<0.2	0.97	<5	260	<5	0.61	<1	6	111	5	2.11	<10	0.54	538	<1	0.10	5	870	14	<5	<20	89	0.12	<10	47	<10	5	44
32	X05409	1.0	0.22	<5	15	<5	0.13	4	12	169	1459	5.52	<10	<0.01	41	127	0.02	7	360	52	<5	<20	15	0.07	<10	6	<10	<1	413
33	X05410	1.1	0.25	<5	10	<5	0.08	3	10	180	1710	3.82	<10	0.02	100	101	0.01	7	190	104	<5	<20	3	0.05	<10	6	<10	<1	211
34	X05411	1.1	0.27	5	35	<5	0.28	<1	10	157	1721	4.17	<10	<0.01	92	105	0.01	4	1130	42	<5	<20	18	0.07	<10	6	<10	<1	84
35	X05412	1.3	0.30	<5	25	<5	0.14	<1	12	177	1946	4.48	<10	0.04	156	160	0.01	6	490	72	<5	<20	5	0.08	<10	6	<10	<1	140
QC DATA:																													
Repeat:																													
1	X05378	2.2	0.52	<5	30	<5	0.25	6	14	83	1703	4.82	<10	0.23	190	93	0.01	5	1160	188	<5	<20	4	0.08	<10	10	<10	<1	730
10	X05387	2.9	0.24	165	30	<5	0.15	6	11	135	2157	5.42	<10	<0.01	69	91	0.01	5	530	148	80	<20	2	0.08	<10	6	<10	<1	607
19	X05396	0.9	0.30	50	25	<5	0.23	<1	9	166	1576	4.29	<10	0.05	137	90	0.01	5	860	48	<5	<20	29	0.07	<10	8	<10	<1	164
Resplit:																													
1	X05378	2.0	0.52	<5	30	<5	0.24	5	14	78	1745	4.90	<10	0.24	197	109	0.01	5	1060	190	<5	<20	5	0.06	<10	10	<10	<1	745
Standard:																													
PB113A		11.5	0.24	40	65	<5	1.63	33	2	5	2195	1.02	<10	0.09	1416	64	0.02	4	90	5506	<5	<20	106	0.03	<10	8	<10	<1	6904

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
dl/5668S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5669

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

22-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07170
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05413	0.97	0.028
2	X05414	0.92	0.027
3	X05415	1.22	0.036
4	X05416	0.48	0.014
5	X05417	0.76	0.022
6	X05418	0.52	0.015
7	X05419	0.38	0.011
8	X05420	0.47	0.014
9	X05421	0.41	0.012
10	X05422	<0.03	<0.001
11	X05423	2.07	0.060
12	X05424	0.87	0.025
13	X05425	0.44	0.013
14	X05426	0.62	0.018
15	X05427	1.11	0.032
16	X05428	0.58	0.017
17	X05429	0.31	0.009
18	X05430	0.42	0.012
19	X05431	0.91	0.027
20	X05432	0.90	0.026
21	X05433	2.07	0.060
22	X05434	0.72	0.021
23	X05435	0.94	0.027
24	X05436	1.19	0.035
25	X05437	0.73	0.021
26	X05438	1.03	0.030
27	X05439	0.84	0.024
28	X05440	0.37	0.011
29	X05441	0.33	0.010

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5669 22-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X05442	0.88	0.026
31	X05443	<0.03	<0.001
32	X05444	0.50	0.015
33	X05445	0.68	0.020
34	X05446	0.94	0.027
35	X05447	0.85	0.025

QC DATA:

Repeat:

1	X05413	0.89	0.026
10	X05422	<0.03	<0.001
11	X05423	1.98	0.058
15	X05427	0.99	0.029
19	X05431	0.94	0.027
21	X05433	2.08	0.061

Resplits:

1	X05413	0.97	0.028

Standard:

OXK48		3.54	0.103

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

23-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5669

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07170
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05413	1.2	0.25	<5	55	<5	0.17	2	11	106	1465	4.39	<10	<0.01	75	102	0.02	3	620	48	<5	<20	29	0.01	<10	5	<10	<1	100
2	X05414	1.4	0.20	<5	50	<5	0.21	3	14	125	1487	5.64	<10	<0.01	57	83	0.02	4	810	92	<5	<20	32	0.01	<10	4	<10	<1	257
3	X05415	1.4	0.16	10	60	<5	0.08	3	13	165	2090	4.10	<10	<0.01	56	137	0.02	4	190	54	<5	<20	30	0.01	<10	4	<10	<1	212
4	X05416	1.0	0.17	25	55	<5	0.13	3	10	164	1145	3.87	<10	<0.01	41	111	0.02	5	470	58	10	<20	34	0.01	<10	4	<10	<1	352
5	X05417	1.9	0.16	70	50	<5	0.12	7	11	178	1538	5.36	<10	<0.01	34	122	0.02	4	400	146	<5	<20	23	0.01	<10	4	<10	<1	910
6	X05418	1.3	0.12	45	50	<5	0.11	2	9	153	1242	3.69	<10	<0.01	30	125	0.02	4	390	84	<5	<20	24	0.01	<10	3	<10	<1	90
7	X05419	1.1	0.11	155	50	<5	0.09	4	8	164	1317	3.72	<10	<0.01	28	80	0.01	4	300	76	20	<20	26	0.01	<10	3	<10	<1	113
8	X05420	1.4	0.11	375	45	<5	0.11	8	9	213	1394	3.48	<10	<0.01	34	109	0.02	6	360	92	20	<20	14	<0.01	<10	4	<10	<1	95
9	X05421	1.7	0.18	110	50	<5	0.11	3	11	174	1394	3.68	<10	<0.01	34	77	0.02	4	350	124	35	<20	16	0.01	<10	4	<10	<1	70
10	X05422	0.2	5.73	40	145	55	0.29	<1	28	44	9	8.60	10	3.75	1783	8	<0.01	<1	1330	112	5	<20	17	0.04	<10	241	<10	3	269
11	X05423	2.5	0.44	20	55	<5	0.04	58	13	170	1757	5.64	<10	0.18	137	89	0.01	8	<10	46	<5	<20	13	0.01	<10	18	<10	<1	1697
12	X05424	2.1	0.13	40	60	<5	0.05	2	10	195	1846	3.77	<10	<0.01	37	62	0.01	6	90	42	15	<20	24	0.01	<10	5	<10	<1	83
13	X05425	1.6	0.14	50	55	<5	0.13	2	9	211	1488	3.08	<10	<0.01	100	81	<0.01	6	60	56	45	<20	13	<0.01	<10	4	<10	<1	36
14	X05426	1.6	0.17	40	55	<5	0.07	2	12	185	1960	3.84	<10	<0.01	48	75	0.01	8	190	34	45	<20	20	0.01	<10	6	<10	<1	49
15	X05427	2.3	0.18	55	45	<5	0.07	2	19	185	2167	4.25	<10	<0.01	68	78	0.01	9	150	54	65	<20	9	0.01	<10	6	<10	<1	68
16	X05428	1.6	0.25	55	60	<5	0.07	1	11	240	1607	4.07	<10	<0.01	63	62	0.01	9	180	86	50	<20	29	0.01	<10	9	<10	<1	45
17	X05429	1.4	0.21	25	45	<5	0.08	1	11	202	1399	4.06	<10	<0.01	40	101	0.01	7	240	52	25	<20	19	0.01	<10	6	<10	<1	24
18	X05430	1.6	0.19	30	40	<5	0.07	1	11	218	1571	3.49	<10	<0.01	47	77	0.01	8	160	40	25	<20	18	<0.01	<10	6	<10	<1	42
19	X05431	1.4	0.20	15	45	<5	0.08	<1	11	181	1779	3.38	<10	<0.01	57	104	0.01	6	190	60	5	<20	17	<0.01	<10	7	<10	<1	47
20	X05432	1.5	0.20	20	55	<5	0.08	1	11	194	2092	3.56	<10	<0.01	44	110	0.01	6	210	40	15	<20	20	<0.01	<10	6	<10	<1	67
21	X05433	1.3	0.18	25	55	<5	0.07	2	8	201	1561	2.90	<10	<0.01	34	302	0.01	5	170	32	10	<20	18	<0.01	<10	5	<10	<1	163
22	X05434	1.4	0.20	15	45	<5	0.04	1	11	240	1792	3.51	<10	<0.01	48	77	0.01	8	20	18	10	<20	17	<0.01	<10	7	<10	<1	24
23	X05435	1.3	0.20	20	55	<5	0.04	<1	11	188	1743	3.28	<10	<0.01	52	92	0.01	4	10	28	5	<20	26	0.01	<10	6	<10	<1	23
24	X05436	2.3	0.19	35	50	<5	0.08	2	15	163	2727	3.58	<10	<0.01	36	146	0.01	7	150	28	15	<20	12	<0.01	<10	5	<10	<1	41
25	X05437	2.2	0.25	10	50	<5	0.07	1	15	205	2457	3.91	<10	<0.01	69	194	0.01	8	110	26	<5	<20	8	<0.01	<10	6	<10	<1	26

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05438	1.7	0.25	10	55	<5	0.05	<1	14	185	1945	4.53	<10	<0.01	60	187	0.01	12	60	34	<5	<20	12	0.01	<10	6	<10	<1	18
27	X05439	1.4	0.27	20	45	<5	0.21	<1	9	169	1789	3.60	<10	0.01	62	96	0.01	6	820	50	<5	<20	15	0.01	<10	6	<10	<1	66
28	X05440	1.1	0.33	10	50	<5	0.13	1	9	214	1554	3.25	<10	0.06	85	73	0.01	9	430	52	<5	<20	10	<0.01	<10	8	<10	<1	38
29	X05441	1.3	0.28	5	50	<5	0.19	2	12	201	2206	3.99	<10	0.03	71	62	0.01	10	700	70	<5	<20	16	<0.01	<10	8	<10	<1	103
30	X05442	0.2	0.80	1375	90	20	0.85	24	29	23	53	4.33	10	1.96	591	4	0.19	97	1120	26	10	<20	53	0.11	<10	22	<10	12	54
31	X05443	<0.2	1.11	10	260	30	0.62	<1	7	108	5	2.15	10	0.62	529	<1	0.13	5	860	24	<5	<20	94	0.14	<10	46	<10	5	39
32	X05444	1.3	0.26	15	65	<5	0.14	<1	11	193	1344	4.10	<10	0.03	72	57	0.01	10	510	138	<5	<20	39	0.01	<10	6	<10	<1	21
33	X05445	1.4	0.28	25	60	<5	0.25	1	12	186	1686	3.80	<10	0.01	60	48	0.01	11	1020	38	<5	<20	19	0.01	<10	7	<10	<1	53
34	X05446	1.8	0.31	20	55	<5	0.14	<1	13	216	1909	4.35	<10	0.04	85	92	0.01	11	480	48	<5	<20	9	0.01	<10	8	<10	<1	24
35	X05447	2.0	0.23	15	50	<5	0.17	4	14	170	2131	4.21	<10	0.01	63	75	<0.01	13	620	138	<5	<20	12	0.01	<10	6	<10	<1	394
QC DATA:																													
Repeat:																													
1	X05413	1.2	0.25	<5	45	<5	0.17	2	11	107	1460	4.41	<10	<0.01	75	97	0.02	2	600	50	<5	<20	23	0.01	<10	5	<10	<1	100
10	X05422	<0.2	5.65	40	140	65	0.29	<1	27	44	9	8.43	10	3.71	1751	9	<0.01	2	1300	108	10	<20	18	0.04	<10	238	<10	3	262
19	X05431	1.3	0.19	10	40	<5	0.08	<1	11	180	1792	3.35	<10	<0.01	53	107	0.01	5	190	58	5	<20	18	<0.01	<10	5	<10	<1	46
Resplit:																													
1	X05413	1.3	0.26	<5	50	<5	0.18	2	12	150	1594	4.54	<10	<0.01	76	114	0.02	3	620	56	<5	<20	27	0.01	<10	5	<10	<1	92
Standard:																													
Pb113A		10.8	0.28	45	70	<5	1.64	38	2	6	2293	1.04	<10	0.11	1499	62	0.02	<1	90	5440	15	<20	83	0.02	<10	8	<10	<1	7133

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5669S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5670

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

22-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07171
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05448	0.65	0.019
2	X05449	0.44	0.013
3	X05450	0.66	0.019
4	X05451	0.91	0.027
5	X05452	1.22	0.036
6	X05453	0.51	0.015
7	X05454	0.44	0.013
8	X05455	0.50	0.015
9	X05456	1.07	0.031
10	X05457	1.20	0.035
11	X05458	0.85	0.025
12	X05459	0.77	0.022
13	X05460	0.62	0.018
14	X05461	0.63	0.018
15	X05462	0.90	0.026
16	X05463	0.88	0.026
17	X05464	0.89	0.026
18	X05465	0.67	0.020
19	X05466	0.81	0.024
20	X05467	0.61	0.018
21	X05468	<0.03	<0.001
22	X05469	0.44	0.013
23	X05470	0.43	0.013
24	X05471	0.35	0.010
25	X05472	0.41	0.012
26	X05473	1.87	0.055
27	X05474	0.80	0.023
28	X05475	0.58	0.017
29	X05476	0.79	0.023

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5670 22-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X05477	0.58	0.017
31	X05478	0.73	0.021
32	X05479	0.66	0.019
33	X05480	0.48	0.014
34	X05481	0.45	0.013
35	X05482	0.29	0.008

QC DATA:

Repeat:

1	X05448	0.64	0.019
10	X05457	1.19	0.035
19	X05466	0.90	0.026

Resplits:

1	X05448	0.61	0.018

Standard:

OxK48		3.52	0.103

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

26-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5670

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07171
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05448	1.5	0.29	35	40	<5	0.21	4	12	159	1260	4.98	<10	<0.01	59	72	0.01	22	900	104	<5	<20	12	<0.01	<10	6	<10	<1	286
2	X05449	0.9	0.29	35	55	<5	0.56	2	7	160	495	3.49	<10	<0.01	42	112	0.01	8	2630	76	<5	<20	45	<0.01	<10	3	<10	4	167
3	X05450	1.3	0.24	45	50	<5	0.10	2	10	199	1352	4.19	<10	0.02	59	88	0.01	13	330	42	10	<20	48	<0.01	<10	4	<10	<1	54
4	X05451	1.7	0.25	25	55	<5	0.15	5	16	167	1978	5.97	10	<0.01	66	72	0.01	23	540	36	5	<20	24	<0.01	<10	5	<10	<1	319
5	X05452	1.8	0.30	15	50	<5	0.20	2	13	181	1922	4.87	<10	0.04	76	77	0.01	19	790	52	<5	<20	30	<0.01	<10	7	<10	2	94
6	X05453	2.4	0.28	70	40	<5	0.11	3	10	195	1579	4.18	<10	0.02	56	85	0.01	13	390	46	5	<20	20	<0.01	<10	4	<10	<1	51
7	X05454	2.2	0.25	60	55	<5	0.11	2	11	183	1350	4.43	<10	0.02	61	83	0.01	13	400	56	10	<20	33	<0.01	<10	4	<10	1	47
8	X05455	2.1	0.26	25	45	<5	0.16	3	13	178	2318	5.10	<10	0.02	55	90	0.01	17	550	42	20	<20	20	<0.01	<10	6	<10	<1	35
9	X05456	2.5	0.28	40	50	<5	0.13	2	12	200	1861	5.35	<10	0.03	75	164	0.01	14	420	38	<5	<20	25	<0.01	<10	5	<10	<1	71
10	X05457	1.9	0.25	20	50	<5	0.14	2	12	143	1781	5.74	<10	<0.01	57	63	0.01	15	500	32	<5	<20	20	<0.01	<10	4	<10	<1	60
11	X05458	1.4	0.34	10	55	<5	0.23	<1	13	188	1533	4.55	<10	0.09	118	104	0.01	12	880	44	<5	<20	33	<0.01	<10	4	<10	2	56
12	X05459	1.8	0.31	10	55	<5	0.19	1	12	164	1418	5.08	<10	0.05	82	44	0.01	15	770	32	<5	<20	19	<0.01	<10	5	<10	<1	44
13	X05460	1.4	0.28	<5	55	<5	0.12	1	12	182	1394	5.09	<10	0.05	77	62	0.01	14	360	32	<5	<20	33	<0.01	<10	4	<10	<1	19
14	X05461	1.8	0.32	15	50	<5	0.12	<1	15	165	1794	5.19	<10	0.09	93	43	0.01	16	380	44	<5	<20	30	<0.01	<10	5	<10	<1	43
15	X05462	2.2	0.31	30	65	<5	0.22	2	16	150	1510	6.38	<10	<0.01	64	67	0.01	18	910	34	<5	<20	33	0.01	<10	5	<10	2	22
16	X05463	1.8	0.30	20	50	<5	0.14	2	14	139	1663	4.95	<10	0.03	59	79	0.01	15	510	28	<5	<20	26	<0.01	<10	4	<10	1	33
17	X05464	2.3	0.34	10	55	<5	0.18	2	15	162	1844	5.43	<10	0.06	72	41	0.01	18	710	28	<5	<20	24	<0.01	<10	5	<10	1	33
18	X05465	2.1	0.31	15	50	<5	0.14	1	13	165	1484	4.69	<10	0.02	55	57	0.01	15	540	34	<5	<20	24	<0.01	<10	5	<10	1	46
19	X05466	2.7	0.24	<5	50	<5	0.13	2	16	141	1902	6.02	<10	<0.01	49	40	<0.01	18	440	28	<5	<20	17	<0.01	<10	3	<10	<1	37
20	X05467	2.2	0.26	10	50	<5	0.13	1	13	163	1557	4.53	<10	0.04	57	34	0.01	14	510	30	<5	<20	20	<0.01	<10	4	<10	<1	34
21	X05468	<0.2	1.06	15	255	15	0.57	<1	7	94	8	2.22	<10	0.60	535	2	0.11	6	920	20	<5	<20	87	0.12	<10	46	<10	6	43
22	X05469	1.8	0.34	10	45	<5	0.17	1	13	168	1305	4.62	<10	0.08	73	80	0.01	16	690	30	<5	<20	20	<0.01	<10	5	<10	<1	53
23	X05470	2.1	0.32	<5	45	<5	0.14	1	14	143	1389	4.63	<10	0.08	62	51	0.01	15	530	34	<5	<20	15	<0.01	<10	5	<10	<1	33
24	X05471	2.5	0.30	5	50	<5	0.18	1	13	152	922	4.97	<10	0.05	61	63	0.01	14	750	44	<5	<20	24	<0.01	<10	5	<10	<1	36
25	X05472	3.2	0.37	<5	45	<5	0.18	2	14	128	1157	5.78	<10	0.12	85	46	0.01	15	740	68	<5	<20	15	0.01	<10	6	<10	<1	57

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05473	3.9	1.14	35	50	<5	0.99	2	22	59	8574	4.13	20	0.66	205	586	0.04	63	110	72	25	<20	60	0.02	<10	43	<10	7	72
27	X05474	5.1	0.33	10	45	<5	0.24	1	14	153	1489	5.52	<10	0.04	78	109	0.01	19	930	76	<5	<20	20	<0.01	<10	7	<10	<1	21
28	X05475	5.3	0.26	<5	40	<5	0.16	2	12	138	1380	4.67	<10	0.03	54	64	0.01	14	640	98	<5	<20	16	<0.01	<10	4	<10	<1	75
29	X05476	5.0	0.30	<5	55	<5	0.18	3	19	130	1951	6.65	10	0.05	64	36	0.01	24	670	40	15	<20	26	<0.01	<10	5	<10	<1	35
30	X05477	5.5	0.32	10	55	<5	0.26	2	17	116	1592	6.41	<10	0.04	68	37	0.01	22	1070	62	<5	<20	23	<0.01	<10	7	<10	<1	45
31	X05478	3.3	0.41	10	50	<5	0.20	1	16	116	1955	5.01	<10	0.13	85	65	0.01	24	800	48	<5	<20	20	<0.01	<10	6	<10	1	49
32	X05479	1.9	1.76	10	55	<5	0.21	1	16	129	1249	5.64	<10	1.27	498	71	0.01	35	860	62	10	<20	24	0.01	<10	24	<10	1	227
33	X05480	3.3	0.73	<5	45	<5	0.15	2	14	129	1396	4.89	<10	0.43	186	57	0.01	25	590	98	<5	<20	15	<0.01	<10	11	<10	<1	130
34	X05481	5.5	0.40	<5	45	<5	0.15	1	14	145	1427	4.78	<10	0.14	86	65	0.01	21	560	86	<5	<20	22	<0.01	<10	6	<10	1	55
35	X05482	2.4	1.09	<5	50	<5	0.29	2	17	127	944	5.54	10	0.73	273	53	0.01	21	1310	76	10	<20	19	0.01	<10	14	<10	3	132
QC DATA:																													
Repeat:																													
1	X05448	1.7	0.31	30	45	<5	0.22	4	13	166	1303	5.02	<10	0.01	63	71	0.01	21	900	104	<5	<20	13	<0.01	<10	6	<10	1	281
10	X05457	1.8	0.26	20	50	<5	0.14	3	13	147	1734	5.78	<10	0.01	58	65	0.01	17	500	32	5	<20	21	<0.01	<10	6	<10	<1	62
19	X05466	2.5	0.27	10	55	<5	0.13	2	16	147	1960	6.13	<10	<0.01	52	39	0.01	18	450	30	<5	<20	20	<0.01	<10	4	<10	<1	36
Resplit:																													
1	X05448	1.8	0.28	35	40	<5	0.21	4	13	160	1353	5.27	<10	<0.01	62	57	0.01	24	840	106	<5	<20	15	<0.01	<10	5	<10	<1	302
Standard:																													
Pb113A		11.2	0.28	65	75	<5	1.64	38	3	7	2282	1.08	<10	0.09	1490	70	0.02	3	90	5452	20	<20	101	0.02	<10	7	<10	2	6938

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5666S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5671

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

23-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07172
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05483	0.36	0.010
2	X05484	0.36	0.010
3	X05485	0.37	0.011
4	X05486	0.36	0.010
5	X05487	0.21	0.006
6	X05488	0.13	0.004
7	X05489	0.14	0.004
8	X05490	0.28	0.008
9	X05491	0.63	0.018
10	X05492	0.38	0.011
11	X05493	0.31	0.009
12	X05494	0.27	0.008
13	X05495	0.23	0.007
14	X05496	0.35	0.010
15	X05497	0.28	0.008
16	X05498	0.26	0.008
17	X05499	0.40	0.012
18	X05500	0.35	0.010
19	X05501	0.51	0.015
20	X05502	0.38	0.011
21	X05503	0.32	0.009
22	X05504	0.42	0.012
23	X05505	0.33	0.010
24	X05506	0.45	0.013
25	X05507	0.42	0.012
26	X05508	0.43	0.013
27	X05509	0.35	0.010
28	X05510	0.51	0.015
29	X05511	0.26	0.008

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5671 23-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X05512	0.38	0.011
31	X05513	<0.03	<0.001
32	X05514	0.42	0.012
33	X05515	0.24	0.007
34	X05516	0.34	0.010
35	X05517	0.19	0.006

QC DATA:

Repeat:

1	X05483	0.35	0.010
10	X05492	0.30	0.009
19	X05501	0.43	0.013

Resplits:

1	X05483	0.30	0.009

Standard:

OXK48		3.52	0.103

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

23-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5671

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07172
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05483	16.4	0.96	<5	50	<5	0.34	1	17	142	1122	5.21	<10	0.67	302	59	0.01	20	860	62	<5	<20	32	0.02	<10	14	<10	<1	77
2	X05484	1.8	1.33	<5	60	<5	0.52	<1	16	107	1003	4.47	<10	1.37	573	59	0.01	17	840	52	5	<20	36	0.02	<10	23	<10	2	81
3	X05485	1.7	1.80	5	45	<5	0.51	<1	16	108	969	4.34	<10	2.01	720	56	0.01	18	860	60	<5	<20	19	0.02	<10	33	<10	<1	60
4	X05486	1.5	2.34	10	60	<5	0.56	<1	20	107	1019	4.92	<10	2.66	760	57	<0.01	39	970	68	10	<20	22	0.02	<10	44	<10	1	93
5	X05487	1.3	2.07	5	55	<5	0.52	<1	14	107	761	4.13	<10	2.25	716	33	<0.01	26	900	52	5	<20	16	0.02	<10	36	<10	<1	82
6	X05488	1.3	0.72	<5	50	<5	0.53	<1	17	96	700	4.13	<10	0.60	392	36	0.01	13	920	50	<5	<20	22	0.02	<10	11	<10	<1	48
7	X05489	1.2	0.49	<5	45	<5	0.42	<1	15	114	649	3.37	<10	0.32	276	76	0.01	14	760	56	<5	<20	22	0.01	<10	6	<10	<1	31
8	X05490	2.0	0.85	10	50	<5	0.38	1	13	96	1035	3.73	<10	0.73	323	57	0.01	20	960	68	10	<20	13	0.01	<10	16	<10	1	81
9	X05491	2.1	1.93	15	55	<5	0.53	1	23	105	1321	5.07	<10	2.16	805	40	0.01	30	800	72	10	<20	15	0.02	<10	36	<10	<1	140
10	X05492	1.5	2.37	10	60	<5	0.97	<1	19	99	860	4.75	<10	3.00	1306	38	0.01	25	980	72	10	<20	16	0.03	<10	39	<10	2	130
11	X05493	1.2	2.01	10	55	<5	1.09	<1	15	96	821	3.86	<10	2.61	1229	48	<0.01	17	910	96	5	<20	20	0.03	<10	33	<10	1	113
12	X05494	1.0	1.49	<5	50	<5	0.88	2	15	114	897	4.88	<10	1.78	1030	53	0.01	15	870	120	<5	<20	13	0.03	<10	27	<10	1	152
13	X05495	1.1	1.43	5	55	<5	0.94	1	14	102	835	3.76	<10	1.72	1103	54	0.01	15	670	102	<5	<20	28	0.02	<10	25	<10	1	113
14	X05496	0.7	1.82	15	60	<5	0.56	<1	13	97	830	3.66	<10	1.97	629	53	0.01	16	1080	60	10	<20	18	0.02	<10	33	<10	2	118
15	X05497	0.8	0.99	<5	45	<5	0.60	1	14	90	776	3.16	<10	1.02	436	51	0.01	16	1020	110	<5	<20	20	0.01	<10	20	<10	<1	159
16	X05498	0.7	0.77	<5	35	<5	0.55	<1	12	118	964	3.21	<10	0.67	286	39	0.01	12	1020	44	<5	<20	13	<0.01	<10	15	<10	<1	79
17	X05499	0.9	1.12	<5	50	<5	0.73	<1	16	115	1322	4.61	<10	0.98	503	34	0.01	6	1380	36	<5	<20	23	0.02	<10	21	<10	<1	51
18	X05500	1.1	1.19	<5	55	<5	0.57	<1	17	106	1189	4.98	<10	1.09	441	66	0.01	6	1400	46	<5	<20	18	0.02	<10	24	<10	<1	51
19	X05501	0.9	1.23	<5	55	<5	0.72	<1	19	109	1208	4.93	<10	1.23	608	129	0.01	8	1230	42	<5	<20	17	0.02	<10	25	<10	<1	41
20	X05502	1.1	0.73	<5	55	<5	0.53	1	18	103	1007	5.49	<10	0.52	304	53	0.01	8	1550	40	<5	<20	17	0.01	<10	12	<10	<1	37
21	X05503	0.7	0.64	<5	50	<5	1.23	<1	15	147	768	4.31	<10	0.78	1046	20	0.01	8	1140	62	<5	<20	23	0.02	<10	10	<10	<1	31
22	X05504	1.1	0.97	<5	45	<5	1.05	<1	20	110	1045	5.74	10	0.90	692	60	0.01	6	1330	68	<5	<20	15	0.02	<10	18	<10	<1	78
23	X05505	0.9	1.86	<5	50	<5	1.04	<1	15	77	841	4.54	<10	2.07	934	85	0.01	3	1570	60	<5	<20	21	0.02	<10	47	<10	2	72
24	X05506	1.1	1.66	<5	55	<5	0.91	1	17	104	1269	5.34	10	1.77	844	40	0.01	6	1360	56	<5	<20	18	0.02	<10	41	<10	<1	71
25	X05507	1.0	0.72	<5	45	<5	0.59	<1	16	133	1271	4.51	<10	0.56	295	50	0.01	9	1030	38	<5	<20	14	0.01	<10	14	<10	<1	39

ICP CERTIFICATE OF ANALYSIS AS 2007-5671

Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05508	0.9	1.06	<5	50	<5	0.56	<1	14	94	777	4.03	<10	1.11	400	74	0.01	19	1220	32	<5	<20	16	0.01	<10	21	<10	<1	62
27	X05509	1.0	1.22	5	55	<5	0.96	<1	14	116	1040	3.63	<10	1.58	874	33	0.01	15	690	58	<5	<20	27	0.02	<10	21	<10	<1	73
28	X05510	0.8	1.77	<5	50	<5	0.76	<1	15	94	1047	4.03	<10	2.20	690	43	0.01	18	870	44	10	<20	13	0.02	<10	34	<10	<1	59
29	X05511	2.6	0.60	50	50	<5	0.89	4	16	125	983	4.29	<10	0.68	599	42	0.01	16	710	78	85	<20	29	0.02	<10	10	<10	<1	77
30	X05512	0.9	1.19	10	120	<5	1.63	<1	14	22	3972	3.34	<10	1.11	689	5	0.17	11	1100	36	5	<20	102	0.16	<10	169	<10	10	41
31	X05513	<0.2	1.01	20	270	35	0.58	<1	8	107	14	2.11	<10	0.60	514	<1	0.10	4	900	32	<5	<20	118	0.15	<10	45	<10	9	40
32	X05514	0.9	0.76	<5	45	<5	1.17	<1	16	131	1063	3.91	<10	1.06	952	52	0.01	16	600	58	<5	<20	22	0.02	<10	14	<10	<1	42
33	X05515	0.7	1.68	15	50	<5	1.06	<1	14	117	937	3.85	<10	2.34	977	57	0.01	20	780	66	10	<20	37	0.02	<10	34	<10	1	106
34	X05516	0.5	2.09	10	55	<5	2.28	<1	13	85	544	3.76	<10	3.39	2306	69	0.01	27	1490	56	15	<20	34	0.03	<10	44	<10	3	139
35	X05517	0.6	0.78	<5	50	<5	1.01	<1	19	105	672	4.25	<10	0.90	704	59	0.01	21	1130	44	5	<20	21	0.02	<10	12	<10	1	31
QC DATA:																													
Repeat:																													
1	X05483	13.3	0.90	<5	50	<5	0.33	1	16	132	1084	5.07	<10	0.65	295	49	0.01	20	860	60	<5	<20	28	0.01	<10	13	<10	<1	75
10	X05492	1.5	2.30	<5	60	<5	0.96	1	19	96	842	4.66	<10	2.93	1282	33	<0.01	24	970	72	10	<20	20	0.03	<10	38	<10	2	127
19	X05501	1.0	1.19	<5	50	<5	0.72	<1	19	106	1215	4.96	<10	1.19	608	106	0.01	7	1270	42	<5	<20	13	0.02	<10	24	<10	<1	41
Resplit:																													
1	X05483	10.5	1.04	<5	50	<5	0.34	<1	17	124	1004	5.13	<10	0.79	323	51	0.01	18	900	52	<5	<20	22	0.01	<10	16	<10	<1	78
Standard:																													
Pb113A		11.0	0.27	50	65	<5	1.66	37	3	6	2241	1.04	<10	0.11	1405	83	0.02	1	90	5394	15	<20	106	0.02	<10	7	<10	<1	6908

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

JJ/nl
df/5669S
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5672

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

26-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07173
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X12001	0.31	0.009
2	X12002	0.52	0.015
3	X12003	0.18	0.005
4	X12004	0.16	0.005
5	X12005	0.25	0.007
6	X12006	0.15	0.004
7	X12007	0.20	0.006
8	X12008	0.12	0.003
9	X12009	0.23	0.007
10	X12010	0.25	0.007
11	X12011	0.31	0.009
12	X12012	0.43	0.013
13	X12013	0.54	0.016
14	X12014	0.35	0.010
15	X12015	0.24	0.007
16	X12016	0.38	0.011
17	X12017	0.33	0.010
18	X12018	0.60	0.017
19	X12019	0.52	0.015
20	X12020	0.47	0.014
21	X12021	0.42	0.012
22	X12022	0.40	0.012
23	X12023	0.31	0.009
24	X12024	0.20	0.006
25	X12025	0.44	0.013
26	X12026	0.30	0.009
27	X12027	0.51	0.015
28	X12028	0.52	0.015
29	X12029	0.30	0.009

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5672 26-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X12030	<0.03	<0.001
31	X12031	0.20	0.006
32	X12032	0.28	0.008
33	X12033	0.40	0.012
34	X12034	0.51	0.015
35	X12035	0.07	0.002

QC DATA:

Repeat:

1	X12001	0.33	0.010
10	X12010	0.27	0.008
19	X12019	0.47	0.014

Resplits:

1	X12001	0.37	0.011

Standard:

OXK48		3.56	0.104

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

26-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5672

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07173
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X12001	1.8	0.89	15	60	<5	2.69	<1	13	56	759	2.48	<10	0.54	701	128	<0.01	2	1160	56	<5	<20	74	0.03	<10	22	<10	7	54
2	X12002	1.9	0.70	10	55	<5	2.17	<1	9	83	1216	2.13	<10	0.40	470	93	<0.01	2	870	38	<5	<20	56	0.02	<10	16	<10	3	36
3	X12003	0.9	1.57	15	115	<5	1.93	<1	15	60	499	3.31	10	1.16	513	65	0.02	3	1780	50	10	<20	82	0.08	<10	43	<10	11	32
4	X12004	1.1	2.45	<5	190	<5	1.24	<1	15	42	386	4.37	10	2.00	862	31	0.01	6	2860	58	15	<20	42	0.09	<10	76	<10	7	72
5	X12005	3.0	1.94	<5	80	<5	2.17	2	24	72	808	7.25	20	1.79	1138	45	<0.01	8	2360	188	<5	<20	55	0.07	<10	70	<10	7	95
6	X12006	3.0	1.24	10	65	<5	2.32	<1	15	51	605	3.50	10	0.93	1193	41	<0.01	2	1560	78	<5	<20	59	0.07	<10	30	<10	8	109
7	X12007	2.3	1.43	20	60	<5	1.40	<1	16	54	685	3.34	10	1.19	877	30	0.01	4	1680	66	10	<20	29	0.09	<10	38	<10	7	133
8	X12008	1.3	1.57	10	100	<5	2.59	<1	14	45	363	3.10	10	1.19	1298	24	0.02	3	1590	36	10	<20	95	0.11	<10	37	<10	9	72
9	X12009	1.7	1.53	20	85	<5	2.28	<1	13	54	544	3.27	10	1.20	1129	43	0.02	2	1540	44	15	<20	85	0.10	<10	39	<10	9	114
10	X12010	3.7	1.39	15	65	<5	2.12	<1	22	58	1141	4.08	10	1.05	924	80	0.02	3	1450	48	<5	<20	73	0.10	<10	37	<10	8	75
11	X12011	3.4	1.24	15	60	<5	2.95	<1	19	82	997	3.53	10	0.95	1207	127	0.01	4	1370	36	10	<20	75	0.10	<10	32	<10	8	91
12	X12012	7.3	0.74	10	60	<5	2.56	2	16	74	2020	4.51	10	0.50	693	44	0.01	5	1230	118	20	<20	63	0.08	<10	25	<10	7	67
13	X12013	3.5	1.33	20	70	<5	2.80	<1	19	77	1373	4.48	10	1.08	980	37	0.03	4	1340	70	10	<20	88	0.08	<10	60	<10	7	116
14	X12014	3.5	1.40	15	70	<5	2.21	1	14	68	998	4.00	10	1.23	1241	50	0.04	4	1490	94	15	<20	84	0.09	<10	58	<10	9	169
15	X12015	2.0	1.32	10	135	<5	2.25	<1	12	47	610	3.60	10	1.07	1117	32	0.04	4	1540	52	10	<20	104	0.09	<10	48	<10	7	134
16	X12016	3.3	1.28	<5	90	<5	2.53	<1	14	66	1011	4.24	10	1.04	1295	27	0.03	3	1420	64	5	<20	105	0.08	<10	46	<10	8	157
17	X12017	2.6	1.22	10	85	<5	2.07	<1	13	60	757	3.83	10	0.92	1058	37	0.02	3	1430	56	10	<20	130	0.06	<10	44	<10	7	145
18	X12018	11.2	1.17	10	65	<5	1.07	8	16	86	1857	4.80	10	0.70	601	59	<0.01	4	1190	310	5	<20	53	0.07	<10	37	<10	8	431
19	X12019	6.2	1.19	15	65	<5	2.04	17	16	56	1263	3.56	10	0.87	1234	43	0.01	2	1510	190	<5	<20	70	0.07	<10	38	<10	6	1033
20	X12020	5.4	1.34	25	85	<5	1.39	<1	14	64	1335	3.52	10	1.11	1187	40	0.02	3	1430	142	<5	<20	71	0.08	<10	47	<10	9	174
21	X12021	13.5	1.38	15	60	<5	1.25	10	15	63	1643	4.03	10	1.23	1198	60	0.02	3	1420	754	10	<20	56	0.07	<10	55	<10	5	748
22	X12022	3.6	1.29	<5	120	<5	1.46	<1	15	69	1155	4.30	20	1.07	1004	42	0.04	3	1410	64	<5	<20	79	0.09	<10	63	<10	5	117
23	X12023	1.7	1.34	5	135	<5	1.88	<1	12	62	786	3.86	10	1.12	1189	25	0.04	<1	1390	42	<5	<20	96	0.10	<10	63	<10	4	124
24	X12024	1.6	1.43	10	80	<5	2.62	<1	13	36	729	3.74	10	1.10	1188	30	0.03	2	1470	122	<5	<20	87	0.07	<10	53	<10	5	124
25	X12025	1.9	1.42	20	95	<5	1.74	<1	17	48	1003	4.52	10	1.11	868	72	0.03	3	1410	48	5	<20	89	0.06	<10	57	<10	5	87

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X12026	1.6	1.40	10	165	<5	1.77	1	15	46	1016	4.58	10	1.12	847	47	0.05	4	1490	42	10	<20	92	0.07	<10	69	<10	7	90
27	X12027	2.7	1.32	15	85	<5	1.47	1	13	59	1552	3.73	10	1.19	814	52	0.03	4	1430	52	15	<20	67	0.07	<10	62	<10	9	104
28	X12028	2.2	1.43	20	70	<5	1.30	<1	15	45	1100	3.39	10	1.16	784	54	0.03	3	1480	54	10	<20	52	0.07	<10	56	<10	7	100
29	X12029	1.7	1.26	10	65	<5	1.85	<1	17	58	978	3.68	10	1.03	746	43	0.03	3	1430	60	<5	<20	66	0.08	<10	52	<10	7	102
30	X12030	0.2	1.01	15	260	15	0.56	<1	6	95	7	2.18	<10	0.61	532	2	0.10	5	910	12	10	<20	89	0.13	<10	47	<10	5	42
31	X12031	1.3	1.40	20	115	<5	1.32	<1	14	45	736	3.23	10	1.17	768	43	0.04	2	1560	80	5	<20	94	0.11	<10	61	<10	8	128
32	X12032	1.3	1.44	10	190	<5	1.34	<1	14	47	837	3.69	10	1.32	847	38	0.04	4	1570	48	<5	<20	89	0.10	<10	73	<10	6	80
33	X12033	1.7	1.23	<5	90	<5	2.13	<1	15	55	1042	4.01	10	1.02	830	46	0.04	4	1460	38	5	<20	89	0.07	<10	68	<10	7	69
34	X12034	2.0	1.35	15	80	<5	1.34	<1	15	61	1189	4.40	10	1.19	894	38	0.03	3	1440	46	<5	<20	65	0.08	<10	69	<10	7	78
35	X12035	0.3	0.81	70	130	<5	0.29	<1	56	243	415	>10	<10	0.18	414	115	0.05	441	90	102	<5	<20	17	<0.01	<10	26	<10	<1	395
QC DATA:																													
Repeat:																													
1	X12001	1.7	0.85	10	55	<5	2.65	<1	12	53	764	2.46	<10	0.54	693	126	<0.01	2	1140	50	<5	<20	65	0.03	<10	21	<10	5	51
10	X12010	3.7	1.34	15	60	<5	2.09	<1	21	55	1144	4.05	10	1.03	918	82	0.02	3	1430	44	5	<20	58	0.09	<10	35	<10	6	76
19	X12019	6.2	1.13	10	55	<5	2.04	17	15	54	1238	3.55	10	0.86	1233	41	0.01	3	1520	190	5	<20	61	0.05	<10	37	<10	5	1047
Resplit:																													
1	X12001	1.7	0.86	15	55	<5	2.54	<1	13	76	785	2.73	<10	0.58	662	146	<0.01	3	1220	42	<5	<20	70	0.03	<10	25	<10	5	66
Standard:																													
PB113A		11.2	0.26	55	65	<5	1.64	36	3	6	2263	1.13	<10	0.11	1475	55	0.02	2	70	5488	10	<20	65	0.01	<10	8	<10	<1	6913

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5669S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5673

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

26-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07174
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X12036	0.37	0.011
2	X12037	0.31	0.009
3	X12038	0.44	0.013
4	X12039	0.26	0.008
5	X12040	0.36	0.010
6	X12041	0.29	0.008
7	X12042	0.44	0.013
8	X12043	1.10	0.032
9	X12044	0.84	0.024
10	X12045	0.46	0.013
11	X12046	0.62	0.018
12	X12047	1.78	0.052
13	X12048	0.39	0.011
14	X12049	0.77	0.022
15	X12050	0.89	0.026
16	X12051	0.88	0.026
17	X12052	0.39	0.011
18	X12053	0.96	0.028
19	X12054	0.90	0.026
20	X12055	1.31	0.038
21	X12056	1.05	0.031
22	X12057	0.50	0.015
23	X12058	0.52	0.015
24	X12059	0.51	0.015
25	X12060	0.37	0.011
26	X12061	0.56	0.016
27	X12062	0.28	0.008
28	X12063	0.35	0.010

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5673 26-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	X12064	0.47	0.014
30	X12065	0.29	0.008
31	X12066	0.51	0.015
32	X12067	0.72	0.021
33	X12068	1.01	0.029
34	X12069	<0.03	<0.001
35	X12070	0.66	0.019

QC DATA:

Repeat:

1	X12036	0.35	0.010
8	X12043	1.20	0.035
10	X12045	0.42	0.012
12	X12047	1.76	0.051
19	X12054	0.86	0.025
20	X12055	1.33	0.039

Resplits:

1	X12036	0.47	0.014

Standard:

OXK48		3.50	0.102

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

26-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 2007-5673

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07174
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X12036	1.9	1.02	<5	55	<5	2.11	2	11	73	1324	3.69	<10	0.87	671	36	0.02	4	1000	38	10	<20	147	0.06	<10	41	<10	4	68
2	X12037	2.1	1.31	<5	75	<5	1.74	<1	17	48	1132	4.17	<10	1.16	831	33	0.03	4	1430	48	<5	<20	73	0.08	<10	63	<10	4	82
3	X12038	1.5	1.36	<5	135	<5	1.83	1	13	54	1137	4.43	<10	1.20	988	40	0.05	4	1350	34	<5	<20	132	0.10	<10	97	<10	3	89
4	X12039	1.2	1.34	<5	275	<5	1.09	<1	14	48	793	3.69	<10	1.22	888	39	0.05	3	1520	34	<5	<20	100	0.11	<10	89	<10	3	97
5	X12040	1.5	1.49	<5	180	<5	1.45	<1	15	38	992	4.27	<10	1.39	972	29	0.05	3	1440	36	<5	<20	87	0.12	<10	96	<10	3	110
6	X12041	1.5	1.29	<5	80	<5	1.79	<1	14	53	821	3.58	<10	1.08	806	32	0.03	3	1380	40	<5	<20	89	0.10	<10	57	<10	3	88
7	X12042	1.4	1.35	<5	85	<5	1.23	1	14	45	1016	4.52	<10	1.26	571	34	0.03	4	1330	42	<5	<20	72	0.11	<10	77	<10	3	84
8	X12043	2.6	1.17	<5	50	<5	1.33	1	16	75	2627	4.45	<10	1.03	472	47	0.03	5	1080	38	5	<20	58	0.08	<10	57	<10	4	87
9	X12044	4.4	0.81	<5	55	<5	1.81	2	21	90	3097	6.04	<10	0.66	520	29	0.02	5	760	166	<5	<20	64	0.09	<10	41	<10	1	124
10	X12045	1.7	1.46	<5	140	<5	1.13	<1	13	39	1132	3.93	<10	1.33	810	34	0.04	3	1460	36	5	<20	74	0.10	<10	67	<10	2	75
11	X12046	2.7	1.36	5	105	<5	1.42	<1	15	70	1808	4.20	<10	1.21	909	41	0.04	3	1250	52	<5	<20	101	0.11	<10	75	<10	3	88
12	X12047	9.9	1.39	<5	75	<5	1.86	35	14	37	1048	3.84	<10	1.24	1125	30	0.03	3	1370	362	<5	<20	77	0.10	<10	58	<10	3	2420
13	X12048	1.4	1.30	<5	215	<5	0.99	1	14	46	1023	3.62	<10	1.11	932	29	0.04	4	1430	36	<5	<20	95	0.10	<10	71	<10	3	121
14	X12049	2.6	1.43	<5	105	<5	0.88	2	15	63	1793	4.64	<10	1.28	929	39	0.05	4	1340	40	<5	<20	88	0.12	<10	91	<10	3	97
15	X12050	2.5	1.42	<5	95	<5	0.92	1	13	55	2092	4.35	<10	1.30	697	38	0.06	4	1310	36	5	<20	71	0.12	<10	105	<10	2	70
16	X12051	2.6	1.29	<5	75	<5	0.88	1	14	66	2372	4.20	<10	1.21	688	39	0.05	4	1250	42	<5	<20	65	0.11	<10	90	<10	3	76
17	X12052	1.0	1.31	<5	150	<5	2.07	<1	14	52	1175	4.15	<10	1.14	987	31	0.05	4	1390	32	<5	<20	81	0.12	<10	94	<10	2	72
18	X12053	2.1	1.29	<5	105	<5	1.66	<1	15	55	1981	4.50	<10	1.18	924	42	0.05	4	1250	40	<5	<20	77	0.11	<10	103	<10	4	84
19	X12054	1.8	1.31	<5	85	<5	1.75	<1	16	49	1926	4.35	<10	1.21	855	49	0.04	4	1250	40	<5	<20	65	0.10	<10	84	<10	3	77
20	X12055	3.8	1.17	<5	45	<5	2.23	1	17	86	2946	5.50	<10	1.01	782	21	0.02	4	930	42	<5	<20	70	0.09	<10	75	<10	<1	67
21	X12056	2.7	1.26	<5	115	<5	2.14	2	16	35	2536	4.66	<10	1.06	926	23	0.03	4	1200	36	5	<20	74	0.09	<10	73	<10	3	80
22	X12057	1.5	1.27	<5	260	<5	2.44	<1	14	46	1123	4.75	<10	1.13	1237	30	0.05	4	1320	36	<5	<20	106	0.11	<10	108	<10	3	82
23	X12058	1.8	1.28	<5	80	<5	2.04	1	16	62	1467	5.14	<10	1.16	1007	32	0.04	4	1290	40	<5	<20	88	0.10	<10	98	<10	4	72
24	X12059	1.8	1.23	<5	75	<5	2.08	<1	16	34	1458	4.92	<10	1.07	1075	33	0.04	4	1280	38	<5	<20	77	0.10	<10	98	<10	3	77
25	X12060	1.0	1.33	<5	365	<5	1.56	1	12	48	947	3.90	<10	1.25	1093	23	0.05	4	1440	34	<5	<20	109	0.11	<10	97	<10	4	104

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X12061	1.5	1.39	<5	95	<5	1.59	2	18	53	1380	5.02	<10	1.32	1099	26	0.06	4	1300	44	5	<20	80	0.11	<10	116	<10	1	117
27	X12062	0.9	1.48	<5	460	<5	1.68	2	12	33	816	4.44	<10	1.45	1235	17	0.05	3	1390	36	<5	<20	113	0.11	<10	108	<10	3	141
28	X12063	1.1	1.47	<5	180	<5	1.34	<1	14	51	1140	4.89	<10	1.40	1248	29	0.05	4	1430	46	<5	<20	97	0.11	<10	105	<10	3	123
29	X12064	1.5	1.30	<5	80	<5	1.58	1	17	69	1378	4.71	<10	1.17	1135	27	0.05	5	1340	40	<5	<20	121	0.11	<10	97	<10	4	104
30	X12065	1.6	1.14	<5	35	<5	2.54	5	16	33	1003	4.54	<10	0.94	1158	34	0.03	4	1350	124	10	<20	80	0.08	<10	51	<10	2	218
31	X12066	1.9	1.39	5	50	<5	2.52	1	15	51	1833	4.32	<10	1.25	1574	26	0.02	5	1250	52	15	<20	137	0.09	<10	58	<10	5	91
32	X12067	2.4	1.29	<5	45	<5	2.18	2	17	75	2496	4.95	<10	1.15	1443	27	0.02	4	1230	58	<5	<20	72	0.09	<10	53	<10	4	92
33	X12068	2.9	1.13	55	65	<5	0.73	3	17	58	3371	3.85	20	0.52	269	215	0.03	13	350	142	35	<20	36	0.04	<10	44	<10	5	158
34	X12069	<0.2	1.06	5	260	20	0.61	<1	7	90	10	2.22	<10	0.62	550	2	0.10	6	860	20	<5	<20	90	0.14	<10	47	<10	3	45
35	X12070	2.7	1.11	5	50	<5	1.71	1	14	60	2014	3.91	<10	0.79	1037	23	<0.01	4	1170	80	<5	<20	63	0.07	<10	28	<10	4	89
QC DATA:																													
Repeat:																													
1	X12036	1.9	1.06	<5	55	<5	2.14	1	11	77	1338	3.76	<10	0.88	680	34	0.02	3	1000	40	5	<20	160	0.07	<10	42	<10	5	68
10	X12045	1.9	1.48	<5	155	<5	1.15	<1	13	41	1125	3.96	<10	1.32	813	34	0.04	3	1460	36	5	<20	84	0.10	<10	69	<10	2	76
19	X12054	2.2	1.35	<5	90	<5	1.80	<1	16	51	1957	4.43	<10	1.24	875	51	0.04	4	1320	44	5	<20	69	0.11	<10	88	<10	3	80
Resplit:																													
1	X12036	2.0	1.07	<5	65	<5	1.94	1	13	64	1394	4.07	<10	0.96	681	37	0.02	4	1070	40	5	<20	145	0.08	<10	47	<10	5	78
Standard:																													
Pb113A		11.4	0.29	50	65	<5	1.73	41	3	6	2318	1.09	<10	0.12	1473	59	0.02	3	70	5674	10	<20	63	0.01	<10	9	<10	<1	6922

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
dl/5667S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5674

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

27-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07175
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X12071	0.82	0.024
2	X12072	1.05	0.031
3	X12073	1.00	0.029
4	X12074	1.17	0.034
5	X12075	0.73	0.021
6	X12076	0.60	0.017
7	X12077	1.29	0.038
8	X12078	1.76	0.051
9	X12079	1.57	0.046
10	X12080	1.39	0.041
11	X12081	0.85	0.025
12	X12082	0.58	0.017
13	X12083	0.49	0.014
14	X12084	0.32	0.009
15	X12085	0.76	0.022
16	X12086	0.58	0.017
17	X12087	0.56	0.016
18	X12088	0.36	0.010
19	X12089	0.49	0.014
20	X12090	<0.03	<0.001
21	X12091	0.49	0.014
22	X12092	1.05	0.031
23	X12093	0.58	0.017
24	X12094	0.38	0.011
25	X12095	0.88	0.026
26	X12096	0.67	0.020
27	X12097	1.01	0.029
28	X12098	0.87	0.025
29	X12099	0.62	0.018

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5674 27-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X12100	0.90	0.026
31	X12101	0.61	0.018
32	X12102	0.51	0.015
33	X12103	0.57	0.017
34	X12104	0.75	0.022
35	X12105	0.73	0.021

QC DATA:

Repeat:

1	X12071	0.86	0.025
10	X12080	1.34	0.039
19	X12089	0.53	0.015

Resplits:

1	X12071	0.82	0.024

Standard:

OXK48		3.53	0.103

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5674

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07175
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X12071	7.4	0.68	10	65	<5	2.74	7	15	113	2535	3.97	<10	0.52	1368	23	<0.01	6	880	76	20	<20	91	0.04	<10	17	<10	5	247
2	X12072	5.4	1.14	<5	75	<5	1.51	4	13	86	3385	4.02	<10	1.00	1302	20	<0.01	6	920	76	25	<20	82	0.04	<10	29	<10	3	169
3	X12073	2.8	1.03	15	60	<5	2.00	3	14	91	2359	4.19	<10	0.85	1078	42	<0.01	8	1330	74	15	<20	83	0.05	<10	31	<10	3	118
4	X12074	3.5	1.03	<5	90	<5	2.56	2	13	70	2866	4.63	<10	0.78	1088	23	0.01	6	1060	76	25	<20	162	0.04	<10	35	<10	4	128
5	X12075	3.0	0.93	<5	115	<5	1.88	2	11	100	2081	3.20	<10	0.61	840	32	<0.01	5	1140	52	10	<20	118	0.03	<10	28	<10	4	111
6	X12076	2.6	1.17	<5	80	<5	1.52	4	14	72	1568	4.67	<10	0.93	997	25	0.01	6	1240	106	15	<20	101	0.04	<10	40	<10	3	210
7	X12077	4.2	1.04	5	80	<5	2.39	5	14	95	1903	4.69	<10	0.80	1069	77	0.01	7	1060	76	25	<20	140	0.04	<10	31	<10	3	132
8	X12078	5.4	0.92	55	80	<5	3.08	4	13	112	2261	3.82	<10	0.78	1321	51	<0.01	7	970	62	30	<20	187	0.04	<10	22	<10	4	102
9	X12079	3.3	0.74	30	75	<5	2.62	3	12	82	2398	2.85	<10	0.39	996	54	<0.01	5	1290	56	10	<20	106	0.04	<10	17	<10	5	82
10	X12080	4.1	0.66	75	60	<5	2.27	6	13	97	2003	3.04	<10	0.33	839	32	<0.01	6	1180	56	15	<20	87	0.03	<10	15	<10	4	137
11	X12081	3.2	0.77	<5	105	<5	2.42	3	14	68	2082	3.86	<10	0.53	896	50	0.01	6	1080	70	25	<20	149	0.03	<10	31	<10	4	106
12	X12082	2.0	0.98	<5	180	<5	1.94	3	10	71	1414	4.96	<10	0.84	988	27	0.02	7	1180	50	20	<20	97	0.05	<10	59	<10	2	130
13	X12083	2.6	1.10	<5	325	<5	1.63	5	11	85	1196	4.64	<10	1.09	1121	30	0.04	7	1270	42	20	<20	94	0.08	<10	96	<10	3	141
14	X12084	1.7	1.19	<5	135	<5	1.93	4	13	84	787	5.05	<10	1.11	1333	21	0.04	7	1330	64	20	<20	149	0.08	<10	95	<10	2	156
15	X12085	3.2	1.08	<5	185	<5	1.70	4	11	87	2182	5.41	<10	0.94	1096	25	0.04	7	1010	48	20	<20	87	0.06	<10	90	<10	2	118
16	X12086	3.0	1.20	<5	105	<5	1.29	3	12	73	2005	4.90	<10	1.08	971	32	0.03	6	1150	68	20	<20	69	0.06	<10	72	<10	3	187
17	X12087	2.9	1.04	<5	165	<5	1.60	4	15	72	1862	4.67	<10	0.91	1002	25	0.04	6	1100	64	15	<20	90	0.07	<10	85	<10	3	164
18	X12088	1.9	1.11	<5	195	<5	1.71	3	11	65	1027	4.56	<10	1.00	1115	20	0.04	8	1330	52	25	<20	104	0.06	<10	84	<10	3	176
19	X12089	2.8	1.13	<5	90	<5	1.77	2	11	58	1701	4.19	<10	1.04	1168	18	0.03	4	1270	50	15	<20	100	0.07	<10	60	<10	2	179
20	X12090	<0.2	1.02	<5	270	20	0.56	<1	7	80	8	2.09	<10	0.58	506	1	0.12	5	860	22	10	<20	97	0.11	<10	44	<10	3	48
21	X12091	2.8	1.02	<5	55	<5	0.76	3	14	84	1584	4.87	<10	0.90	1054	24	0.02	6	1210	58	15	<20	57	0.05	<10	52	<10	<1	158
22	X12092	12.7	1.17	<5	70	<5	1.01	5	14	82	3258	6.36	<10	1.07	1455	30	0.02	12	1090	114	50	<20	75	0.04	<10	56	<10	1	139
23	X12093	4.2	0.83	<5	55	<5	0.75	2	12	67	1907	3.91	<10	0.61	833	23	<0.01	5	1280	74	15	<20	55	0.04	<10	27	<10	2	139
24	X12094	2.8	0.79	<5	60	<5	0.72	3	12	72	1509	3.93	<10	0.52	690	32	<0.01	5	1320	68	15	<20	38	0.03	<10	26	<10	2	130
25	X12095	3.3	0.91	<5	80	<5	0.79	2	12	96	2204	4.07	<10	0.68	780	29	<0.01	6	1030	48	15	<20	48	0.04	<10	37	<10	2	118

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X12096	2.8	1.02	<5	120	<5	1.50	3	14	72	1994	4.63	<10	0.81	805	27	0.03	6	1280	56	20	<20	114	0.05	<10	53	<10	3	142
27	X12097	5.3	0.75	<5	65	<5	1.98	3	16	94	3387	4.47	<10	0.53	878	19	<0.01	6	780	54	15	<20	95	0.04	<10	24	<10	2	134
28	X12098	4.4	0.79	<5	65	<5	1.36	3	16	63	3080	4.99	<10	0.60	691	20	<0.01	6	1040	108	15	<20	70	0.04	<10	38	<10	2	124
29	X12099	2.3	0.92	<5	85	<5	1.69	2	12	82	1654	4.21	<10	0.84	831	27	0.02	6	1110	46	15	<20	91	0.05	<10	54	<10	3	102
30	X12100	0.3	0.70	1525	90	20	0.83	3	30	24	58	4.64	10	2.07	633	5	0.16	113	1210	22	20	<20	50	0.09	<10	23	<10	10	65
31	X12101	2.9	0.93	<5	55	<5	1.71	4	13	75	1754	4.16	<10	0.70	928	21	<0.01	6	1270	60	20	<20	60	0.04	<10	29	<10	2	181
32	X12102	2.4	0.95	<5	105	<5	1.37	2	12	94	1604	4.10	<10	0.86	857	23	0.03	6	1150	48	20	<20	88	0.06	<10	66	<10	3	97
33	X12103	5.8	0.75	<5	60	<5	2.29	4	11	66	3529	4.24	<10	0.54	876	20	<0.01	7	1110	50	30	<20	71	0.03	<10	31	<10	3	82
34	X12104	3.3	0.62	20	55	<5	1.68	3	13	73	1981	3.31	<10	0.30	643	19	<0.01	5	1230	42	5	<20	48	0.03	<10	17	<10	3	88
35	X12105	4.4	0.76	10	65	<5	0.97	2	16	81	2233	4.52	<10	0.42	528	23	<0.01	8	1110	44	20	<20	41	0.03	<10	22	<10	1	81
QC DATA:																													
Repeat:																													
1	X12071	7.3	0.75	10	65	<5	2.90	7	15	123	2715	4.21	<10	0.57	1464	27	<0.01	8	920	76	20	<20	91	0.04	<10	18	<10	4	261
10	X12080	4.0	0.72	80	60	<5	2.34	6	13	103	2084	3.13	<10	0.35	867	32	<0.01	5	1190	56	10	<20	91	0.04	<10	17	<10	4	142
19	X12089	2.9	1.12	<5	90	<5	1.76	2	11	59	1656	4.20	<10	1.03	1163	19	0.03	4	1260	52	20	<20	103	0.06	<10	61	<10	3	180
Resplit:																													
1	X12071	7.3	0.64	10	55	<5	2.74	4	14	116	2473	4.19	<10	0.49	1465	23	<0.01	8	860	74	20	<20	100	0.04	<10	16	<10	4	246
Standard:																													
Pb113A		11.6	0.25	50	55	<5	1.71	40	2	5	2308	1.01	<10	0.10	1397	67	0.02	2	90	5446	25	<20	108	0.01	<10	6	<10	<1	6964

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5674S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5675

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

27-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07177
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X12141	0.94	0.027
2	X12142	0.48	0.014
3	X12143	0.81	0.024
4	X12144	0.63	0.018
5	X12145	0.43	0.013
6	X12146	0.75	0.022
7	X12147	0.57	0.017
8	X12148	0.91	0.027
9	X12149	0.59	0.017
10	X12150	0.64	0.019
11	X12151	0.98	0.029
12	X12152	1.42	0.041
13	X12153	0.74	0.022
14	X12154	0.61	0.018
15	X12155	1.14	0.033
16	X12156	0.58	0.017
17	X12157	0.56	0.016
18	X12158	0.57	0.017
19	X12159	0.48	0.014
20	X12160	0.54	0.016
21	X12161	0.51	0.015
22	X12162	0.49	0.014
23	X12163	0.76	0.022
24	X12164	0.63	0.018
25	X12165	0.67	0.020
26	X12166	0.61	0.018
27	X12167	0.80	0.023
28	X12168	0.59	0.017
29	X12169	0.97	0.028

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5675 27-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X12170	0.70	0.020
31	X12171	0.61	0.018
32	X12172	0.93	0.027
33	X12173	0.86	0.025
34	X12174	0.28	0.008
35	X12175	<0.03	<0.001

QC DATA:

Repeat:

1	X12141	0.93	0.027
10	X12150	0.58	0.017
19	X12159	0.53	0.015

Resplits:

1	X12141	0.87	0.025

Standard:

OXK48		3.56	0.104

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

27-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5675

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07177
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X12141	3.2	0.85	25	50	<5	2.06	2	12	160	2122	5.00	<10	0.50	1028	12	0.01	3	720	34	<5	<20	54	<0.01	<10	26	<10	4	89
2	X12142	2.0	0.76	20	75	<5	1.39	2	9	108	1243	3.82	<10	0.45	743	15	0.01	2	1110	16	<5	<20	45	0.01	<10	28	<10	4	57
3	X12143	1.9	0.89	10	110	<5	1.45	2	7	96	1465	5.36	<10	0.69	668	12	0.03	1	1100	14	<5	<20	215	0.03	<10	66	<10	4	72
4	X12144	2.8	0.61	10	65	<5	1.88	2	8	105	1894	4.73	<10	0.41	728	11	0.02	<1	890	14	<5	<20	143	0.01	<10	35	<10	4	65
5	X12145	2.5	0.51	10	50	<5	0.90	2	8	129	1824	4.40	<10	0.35	448	13	0.02	1	660	14	<5	<20	94	<0.01	<10	35	<10	2	64
6	X12146	2.5	0.83	15	55	<5	1.82	2	9	106	2056	4.54	<10	0.60	748	13	0.02	2	1040	26	<5	<20	123	0.01	<10	38	<10	5	81
7	X12147	2.4	0.71	10	65	<5	2.04	2	8	115	1794	4.40	<10	0.57	569	9	0.03	2	1100	14	<5	<20	233	0.02	<10	50	<10	5	52
8	X12148	2.2	0.88	15	60	<5	1.97	4	8	97	1423	5.51	<10	0.72	745	12	0.02	<1	1140	114	<5	<20	137	0.03	<10	51	<10	5	159
9	X12149	2.1	0.68	15	55	<5	1.55	2	8	153	1468	5.07	<10	0.52	570	11	0.02	3	920	22	<5	<20	123	0.04	<10	46	<10	4	62
10	X12150	2.6	0.77	10	75	<5	2.46	3	8	96	1932	5.01	<10	0.65	661	10	0.03	2	1190	24	<5	<20	200	0.05	<10	59	<10	5	71
11	X12151	3.9	0.85	15	55	<5	1.57	3	7	142	2655	4.79	<10	0.58	653	10	0.02	2	1060	40	<5	<20	109	0.02	<10	40	<10	4	100
12	X12152	3.7	1.05	25	55	<5	0.79	2	10	108	2801	4.92	<10	0.69	622	8	0.01	<1	930	16	<5	<20	31	<0.01	<10	30	<10	3	101
13	X12153	2.4	0.96	15	110	<5	1.34	2	8	133	1501	4.65	<10	0.69	765	10	0.01	2	980	16	<5	<20	66	<0.01	<10	36	<10	3	73
14	X12154	3.1	1.07	15	70	<5	2.10	2	9	126	1831	5.08	<10	0.91	1144	9	0.02	2	940	26	<5	<20	82	<0.01	<10	36	<10	3	66
15	X12155	2.9	1.56	55	60	<5	2.02	3	10	99	1952	6.50	<10	1.37	1363	9	0.02	1	1020	60	<5	<20	68	<0.01	<10	50	10	4	103
16	X12156	1.8	0.88	30	55	<5	1.92	2	12	112	982	4.45	<10	0.61	916	10	0.01	2	1010	32	<5	<20	74	<0.01	<10	31	<10	3	94
17	X12157	1.6	0.52	20	55	<5	1.53	2	8	135	1100	4.02	<10	0.29	568	9	0.02	2	860	28	<5	<20	84	0.02	<10	35	<10	3	51
18	X12158	1.9	0.95	20	70	<5	1.33	3	7	116	1194	5.42	<10	0.72	661	10	0.02	1	990	18	<5	<20	81	0.03	<10	55	<10	4	91
19	X12159	1.8	0.89	15	110	<5	1.92	2	8	95	1253	5.11	<10	0.69	804	13	0.02	1	1140	16	<5	<20	109	0.04	<10	59	<10	5	75
20	X12160	1.7	0.87	15	75	<5	1.98	2	11	79	1293	4.57	<10	0.63	714	12	0.02	1	1190	18	<5	<20	138	0.04	<10	48	<10	5	53
21	X12161	1.9	0.82	15	60	<5	0.70	2	9	130	1336	4.61	<10	0.55	533	11	0.01	1	770	14	<5	<20	29	0.01	<10	45	<10	3	70
22	X12162	1.3	0.56	10	100	<5	1.21	2	6	105	876	4.64	<10	0.38	503	11	0.02	<1	920	14	<5	<20	159	0.03	<10	51	<10	3	44
23	X12163	1.4	0.76	10	60	<5	1.44	2	11	135	961	4.73	<10	0.55	697	10	0.02	2	820	16	<5	<20	64	0.02	<10	51	<10	4	62
24	X12164	2.1	0.83	15	60	<5	1.19	2	9	127	1514	4.28	<10	0.61	671	12	0.02	2	1060	16	<5	<20	55	0.02	<10	46	<10	4	63
25	X12165	2.2	0.70	15	50	<5	1.37	2	9	132	1503	4.59	<10	0.57	666	9	0.02	2	810	26	<5	<20	73	0.02	<10	46	<10	3	65

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X12166	1.9	0.88	15	60	<5	1.15	2	7	100	1565	4.43	<10	0.76	693	8	0.02	1	940	18	<5	<20	80	0.02	<10	51	<10	4	72
27	X12167	2.6	0.79	20	60	<5	1.48	3	9	109	1653	5.53	<10	0.67	767	10	0.02	1	950	30	<5	<20	98	0.03	<10	69	<10	4	125
28	X12168	2.4	0.74	20	50	<5	1.23	2	11	168	1791	4.74	<10	0.57	665	9	0.02	2	790	26	<5	<20	80	0.02	<10	47	<10	3	68
29	X12169	2.4	0.85	20	70	<5	1.32	3	9	162	1885	5.80	<10	0.67	722	9	0.02	2	890	22	<5	<20	118	0.02	<10	70	<10	3	78
30	X12170	2.5	0.79	15	50	<5	1.45	3	16	144	1866	5.43	<10	0.67	655	9	0.02	1	800	24	<5	<20	99	0.01	<10	57	<10	3	67
31	X12171	2.6	0.73	15	45	<5	0.79	4	15	140	2092	5.35	<10	0.59	631	8	0.02	1	650	20	<5	<20	34	<0.01	<10	53	<10	2	128
32	X12172	0.3	0.74	1390	90	<5	0.86	1	25	22	49	4.60	10	1.97	589	<1	0.17	101	1220	16	5	<20	50	0.09	<10	19	<10	11	59
33	X12173	3.1	0.80	20	55	<5	1.14	3	8	136	1582	5.92	<10	0.70	814	8	0.02	1	760	28	<5	<20	63	<0.01	<10	77	<10	3	101
34	X12174	2.8	1.14	30	60	<5	0.93	3	17	55	2599	3.49	20	0.63	188	183	0.03	12	580	46	5	<20	60	0.04	<10	40	<10	8	273
35	X12175	<0.2	1.05	10	255	<5	0.62	<1	6	116	6	2.26	<10	0.61	534	<1	0.11	7	880	<2	<5	<20	117	0.14	<10	41	<10	5	45
QC DATA:																													
Repeat:																													
1	X12141	3.2	0.79	25	45	<5	2.03	2	11	149	2001	4.86	<10	0.49	978	11	0.01	2	680	32	<5	<20	52	<0.01	<10	25	<10	4	83
10	X12150	2.7	0.72	10	70	<5	2.34	3	8	90	1843	4.87	<10	0.64	635	9	0.03	2	1140	24	<5	<20	188	0.04	<10	57	<10	4	69
19	X12159	1.8	0.80	15	100	<5	1.80	2	7	86	1142	4.81	<10	0.66	743	12	0.02	1	1050	14	<5	<20	101	0.03	<10	55	<10	4	70
Resplit:																													
1	X12141	3.2	0.78	20	50	<5	2.19	3	11	152	2132	4.76	<10	0.43	1075	12	0.01	2	680	32	<5	<20	53	<0.01	<10	23	<10	5	95
Standard:																													
Pb113A		11.4	0.27	40	70	<5	1.69	38	2	<1	2339	1.07	<10	0.11	1476	66	0.02	<1	100	5514	<5	<20	88	0.01	<10	6	<10	1	6979

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
dl/n5675S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5679

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07176
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X12106	1.08	0.031
2	X12107	0.92	0.027
3	X12108	0.90	0.026
4	X12109	1.01	0.029
5	X12110	0.95	0.028
6	X12111	0.65	0.019
7	X12112	0.68	0.020
8	X12113	0.96	0.028
9	X12114	0.83	0.024
10	X12115	0.74	0.022
11	X12116	1.05	0.031
12	X12117	0.78	0.023
13	X12118	1.13	0.033
14	X12119	0.83	0.024
15	X12120	0.45	0.013
16	X12121	0.85	0.025
17	X12122	0.68	0.020
18	X12123	0.97	0.028
19	X12124	1.15	0.034
20	X12125	0.63	0.018
21	X12126	1.76	0.051
22	X12127	0.95	0.028
23	X12128	0.85	0.025
24	X12129	1.28	0.037
25	X12130	1.64	0.048
26	X12131	0.76	0.022
27	X12132	1.09	0.032
28	X12133	0.73	0.021
29	X12134	0.74	0.022

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X12135	<0.03	<0.001
31	X12136	0.65	0.019
32	X12137	0.59	0.017
33	X12138	0.66	0.019
34	X12139	0.66	0.019
35	X12140	1.01	0.029

QC DATA:

Repeat:

1	X12106	1.06	0.031
10	X12115	0.75	0.022
19	X12124	1.05	0.031

Resplits:

1	X12106	1.02	0.030

Standard:

OXK48		3.50	0.102

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 2007-5679

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07176
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X12106	2.3	0.96	10	60	<5	1.84	2	12	113	1736	3.91	<10	0.72	904	30	0.02	7	1140	44	20	<20	115	0.04	<10	50	<10	3	83
2	X12107	3.3	0.98	5	60	<5	1.54	2	15	81	2642	5.34	10	0.88	848	26	0.02	8	960	48	20	<20	112	0.05	<10	65	<10	4	76
3	X12108	2.3	1.00	<5	95	<5	2.01	2	14	98	1946	5.01	10	0.89	911	29	0.04	8	1160	46	15	<20	191	0.07	<10	80	<10	4	82
4	X12109	3.6	0.82	<5	65	<5	1.54	2	15	123	2631	5.12	<10	0.76	654	31	0.02	9	770	34	25	<20	242	0.05	<10	65	<10	3	67
5	X12110	3.4	0.73	5	100	<5	2.05	2	14	95	1923	4.56	<10	0.62	858	26	0.04	7	1140	44	15	<20	220	0.07	<10	92	<10	6	65
6	X12111	2.0	0.92	10	70	<5	1.67	1	13	101	1339	3.71	<10	0.87	855	28	0.04	7	1330	36	10	<20	202	0.06	<10	74	<10	5	85
7	X12112	2.3	0.92	<5	80	<5	1.15	2	13	113	1606	5.27	<10	0.76	706	25	0.03	9	1130	38	20	<20	109	0.05	<10	75	<10	3	86
8	X12113	2.3	0.75	5	75	<5	1.21	2	12	126	1529	4.63	<10	0.59	682	25	0.03	8	1130	34	15	<20	161	0.05	<10	74	<10	3	80
9	X12114	2.5	0.93	5	75	<5	1.27	3	14	99	1593	5.77	10	0.81	837	31	0.03	11	1070	70	30	<20	128	0.06	<10	93	<10	3	121
10	X12115	2.7	0.97	<5	70	<5	2.85	3	16	118	2004	5.51	10	0.93	1170	24	0.02	9	980	34	30	<20	235	0.05	<10	64	<10	2	101
11	X12116	5.8	0.83	5	55	<5	2.49	3	18	115	2104	5.35	10	0.61	997	40	0.01	13	1040	66	30	<20	133	0.04	<10	44	<10	3	71
12	X12117	2.9	0.58	<5	60	<5	0.80	3	16	147	1932	5.68	<10	0.37	478	31	0.02	11	800	36	20	<20	49	0.04	<10	55	<10	2	65
13	X12118	2.6	0.86	<5	65	<5	0.69	3	17	128	2011	6.00	10	0.66	591	29	0.03	11	960	68	25	<20	59	0.04	<10	75	<10	2	102
14	X12119	3.1	0.73	<5	70	<5	0.98	2	14	142	1813	4.90	<10	0.51	641	24	0.02	9	980	44	10	<20	79	0.04	<10	56	<10	2	84
15	X12120	2.2	1.11	5	65	<5	1.17	2	13	101	1256	4.67	<10	0.85	943	17	0.02	7	1260	42	15	<20	166	0.05	<10	51	<10	2	125
16	X12121	10.3	0.93	<5	55	<5	1.83	3	14	128	4317	5.71	10	0.63	1129	22	<0.01	11	960	100	25	<20	69	0.02	<10	31	<10	3	110
17	X12122	3.3	0.93	<5	60	<5	1.19	3	12	129	2121	5.37	<10	0.56	693	26	<0.01	10	790	38	25	<20	63	0.02	<10	38	<10	2	89
18	X12123	2.7	0.93	15	70	<5	1.25	3	14	133	1567	5.65	<10	0.58	654	27	0.01	11	1090	48	25	<20	70	0.03	<10	44	<10	3	90
19	X12124	6.8	0.68	<5	60	<5	0.96	3	15	211	5057	5.99	<10	0.41	551	23	0.01	11	530	38	15	<20	67	0.02	<10	44	<10	<1	66
20	X12125	2.6	0.85	10	85	<5	1.68	2	11	108	1562	5.56	<10	0.59	952	21	0.01	8	1020	68	10	<20	109	0.04	<10	52	<10	2	144
21	X12126	8.0	0.63	10	65	<5	1.30	14	17	135	5189	6.28	<10	0.36	874	20	<0.01	10	670	58	15	<20	98	0.02	<10	35	<10	2	543
22	X12127	2.4	0.83	<5	70	<5	0.71	5	12	120	1661	6.79	10	0.57	551	29	0.02	15	1320	30	45	<20	57	0.02	<10	69	<10	2	105
23	X12128	2.1	0.77	5	65	<5	1.24	3	12	128	1528	5.69	<10	0.55	618	21	0.02	9	1040	44	20	<20	101	0.05	<10	63	<10	2	81
24	X12129	5.0	0.62	<5	60	<5	1.26	2	14	131	3932	5.97	<10	0.42	630	22	0.01	8	730	30	10	<20	91	0.04	<10	58	<10	2	55
*25	X12130	<0.2	0.70	2210	75	20	0.81	31	30	27	60	4.99	20	1.81	751	4	0.16	110	1110	28	15	<20	60	0.09	<10	24	<10	11	61

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X12131	3.2	0.89	<5	65	<5	0.67	2	21	115	2231	7.17	<10	0.66	546	22	0.02	8	960	34	15	<20	59	0.06	<10	76	<10	2	63
27	X12132	4.4	0.79	<5	80	<5	1.66	4	15	126	3139	7.13	10	0.63	756	23	0.02	11	810	38	25	<20	188	0.05	<10	107	<10	2	104
28	X12133	2.6	0.85	10	55	<5	1.26	3	12	154	1459	5.32	<10	0.58	770	24	<0.01	10	780	40	25	<20	71	0.03	<10	41	<10	1	62
29	X12134	2.3	0.83	20	60	<5	1.79	4	13	112	1597	5.49	<10	0.66	858	24	0.02	12	980	30	30	<20	108	0.05	<10	58	<10	3	57
30	X12135	<0.2	0.98	15	255	20	0.59	<1	7	90	6	2.14	<10	0.55	613	2	0.10	6	990	16	<5	<20	99	0.10	<10	46	<10	7	47
31	X12136	2.6	0.75	15	60	<5	2.08	2	13	110	1551	4.97	<10	0.52	820	20	0.02	8	1010	52	10	<20	223	0.03	<10	52	<10	3	70
32	X12137	2.1	0.68	10	65	<5	1.66	2	11	123	1372	5.20	<10	0.46	599	22	0.02	8	1000	26	15	<20	258	0.04	<10	53	<10	3	73
33	X12138	2.2	0.75	15	70	<5	2.54	3	14	146	1536	5.16	10	0.59	785	23	0.03	12	1070	32	35	<20	274	0.04	<10	73	<10	4	62
34	X12139	2.6	0.80	10	60	<5	1.37	3	13	143	1414	4.90	<10	0.53	747	23	0.01	11	880	38	25	<20	91	0.03	<10	36	<10	2	84
35	X12140	3.7	1.09	55	70	<5	0.67	5	16	56	3283	3.61	20	0.45	247	204	0.03	15	410	144	40	<20	32	0.03	<10	40	<10	6	166
QC DATA:																													
Repeat:																													
1	X12106	2.5	0.98	10	70	<5	1.86	2	13	117	1722	3.98	<10	0.71	913	34	0.02	7	1190	40	10	<20	124	0.05	<10	52	<10	5	86
10	X12115	2.5	0.93	<5	70	<5	2.68	2	15	116	1944	5.25	10	0.86	1105	22	0.02	9	940	38	25	<20	219	0.06	<10	62	<10	3	97
19	X12124	6.7	0.71	5	65	<5	0.95	3	15	219	5060	5.99	<10	0.42	553	23	0.01	12	510	40	15	<20	75	0.02	<10	47	<10	<1	65
Resplit:																													
1	X12106	2.3	0.99	20	60	<5	1.80	3	15	101	1735	4.11	<10	0.74	911	29	0.02	10	1210	44	20	<20	128	0.04	<10	54	<10	4	92
Standard:																													
PB113A		11.6	0.28	45	70	<5	1.71	31	2	7	2265	1.08	<10	0.11	1435	70	0.02	4	100	5582	20	<20	82	<0.01	<10	9	<10	<1	7071

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
di/5679
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5680

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07179
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	X10077	0.46	0.013		
2	X10078	0.20	0.006		
3	X10079	0.49	0.014		
4	X10080	0.76	0.022		
5	X10081	0.50	0.015		
6	X10082	0.44	0.013		
7	X10083	0.60	0.017		
8	X10084	0.50	0.015		
9	X10085	0.35	0.010		
10	X10086	0.57	0.017		
11	X10087	0.58	0.017		
12	X10088	0.67	0.020		
13	X10089	0.54	0.016		
14	X10090	0.40	0.012		
15	X10091	0.64	0.019		
16	X10092	1.14	0.033		
17	X10093	0.75	0.022		
18	X10094	0.53	0.015		
19	X10095	0.88	0.026		
20	X10096	0.59	0.017		
21	X10097	0.48	0.014		
22	X10098	0.70	0.020		
23	X10099	0.90	0.026		
24	X10100	1.19	0.035		
25	X10101	0.71	0.021		
26	X10102	0.72	0.021		
27	X10103	<0.03	<0.001		
28	X10104	0.99	0.029		
29	X10105	0.65	0.019		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5680 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
30	X10106	0.46	0.013		
31	X10107	0.40	0.012		
32	X10108	2.25	0.066	34.5	1.01
33	X10109	0.88	0.026		
34	X10110	0.66	0.019		
35	X10111	0.63	0.018		
QC DATA:					
Repeat:					
1	X10077	0.47	0.014		
10	X10086	0.56	0.016		
19	X10095	0.84	0.024		
24	X10100	1.06	0.031		
32	X10108	2.27	0.066		
Resplits:					
1	X10077	0.52	0.015		
Standard:					
OXK48		3.53	0.103		
Pb113				22.2	0.65

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 2007-5680

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07179
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10077	2.1	1.30	<5	55	<5	2.38	3	17	65	1314	4.31	<10	1.21	702	73	0.05	7	1330	34	25	<20	110	0.06	<10	77	<10	2	72
2	X10078	1.6	1.23	<5	75	<5	2.83	2	12	58	1259	3.30	<10	1.10	789	47	0.04	4	1380	34	15	<20	107	0.05	<10	55	<10	4	91
3	X10079	1.7	1.11	<5	55	<5	1.95	2	12	46	1163	4.03	<10	1.04	754	30	0.02	5	1520	30	15	<20	96	0.02	<10	44	<10	3	91
4	X10080	3.1	1.00	<5	60	<5	1.89	3	15	66	2358	4.56	<10	1.00	737	20	0.03	7	1220	40	15	<20	90	0.02	<10	37	<10	4	98
5	X10081	1.5	1.22	<5	65	<5	1.67	2	14	55	1200	4.19	<10	1.27	655	19	0.04	5	1490	40	10	<20	102	0.02	<10	55	<10	3	147
6	X10082	1.3	1.22	<5	70	<5	2.56	2	13	53	1077	3.77	<10	1.38	931	27	0.04	4	1520	34	20	<20	154	0.02	<10	48	<10	3	105
7	X10083	2.3	0.46	5	50	<5	2.26	3	12	103	1956	3.68	<10	0.45	853	25	<0.01	6	1030	36	10	<20	84	0.02	<10	16	<10	2	92
8	X10084	2.8	0.25	25	40	<5	1.30	5	12	108	1858	3.52	<10	0.20	477	24	<0.01	5	990	36	20	<20	44	0.01	<10	9	<10	2	187
9	X10085	1.6	0.38	<5	70	<5	2.92	2	13	88	1268	3.47	<10	0.52	953	15	0.01	4	1300	44	<5	<20	146	0.03	<10	19	<10	5	84
10	X10086	1.8	0.63	<5	60	<5	3.12	2	10	66	1404	3.05	<10	0.76	1187	17	0.01	4	1350	26	10	<20	152	0.02	<10	20	<10	4	75
11	X10087	1.9	0.45	5	40	<5	2.74	5	13	68	1133	2.97	<10	0.52	1112	25	<0.01	7	1490	142	15	<20	122	0.01	<10	18	<10	4	124
12	X10088	1.6	0.60	<5	40	<5	2.75	2	12	87	1323	2.85	<10	0.74	1112	26	<0.01	5	1360	22	5	<20	121	0.02	<10	16	<10	2	63
13	X10089	2.2	0.47	<5	40	<5	2.92	3	16	77	1739	3.99	<10	0.84	1549	21	<0.01	7	1300	94	10	<20	142	0.02	<10	17	<10	4	92
14	X10090	1.5	0.65	<5	75	<5	2.50	2	11	80	1200	2.99	<10	0.66	1068	21	0.02	4	1360	22	<5	<20	173	0.02	<10	23	<10	3	51
15	X10091	2.0	0.52	<5	50	<5	2.24	1	14	134	1665	3.19	<10	0.62	1106	19	<0.01	5	1150	26	<5	<20	112	0.02	<10	17	<10	5	34
16	X10092	3.7	0.37	5	40	<5	1.60	2	19	130	3450	4.26	<10	0.25	631	30	<0.01	7	720	36	<5	<20	76	0.01	<10	11	<10	<1	32
17	X10093	1.8	0.75	<5	50	<5	2.05	2	12	97	1721	3.88	<10	0.84	805	17	0.02	7	1160	26	10	<20	116	0.02	<10	29	<10	4	52
18	X10094	1.7	0.46	<5	50	<5	2.52	1	11	71	1304	3.15	<10	0.59	1005	15	0.01	5	1440	16	10	<20	93	0.02	<10	17	<10	3	28
19	X10095	3.9	0.43	<5	45	<5	2.60	3	13	89	2579	4.01	<10	0.72	1416	14	<0.01	6	1260	40	10	<20	101	0.02	<10	15	<10	4	45
20	X10096	1.4	0.79	<5	45	<5	1.21	2	14	66	1189	3.71	<10	0.86	1016	18	0.01	6	1410	30	10	<20	61	0.02	<10	25	<10	4	70
21	X10097	1.6	0.98	<5	55	<5	0.99	2	12	77	1422	3.97	<10	0.99	877	23	0.03	6	1490	36	15	<20	58	0.02	<10	39	<10	3	71
22	X10098	2.3	0.86	<5	45	<5	1.43	3	15	81	1682	3.77	<10	1.04	1167	21	0.01	8	1330	52	25	<20	70	0.02	<10	26	<10	3	70
23	X10099	3.6	0.54	<5	35	<5	1.34	2	14	91	2798	4.29	<10	0.64	939	19	<0.01	7	1220	72	10	<20	48	0.02	<10	19	<10	3	65
24	X10100	3.6	0.29	10	40	<5	2.19	3	15	102	2812	4.23	<10	0.50	1430	16	<0.01	7	1060	78	10	<20	113	0.02	<10	17	<10	3	71
25	X10101	2.1	0.58	5	40	<5	2.16	3	12	82	1856	3.35	<10	0.83	1393	17	<0.01	5	1330	22	15	<20	70	0.02	<10	19	<10	4	90

ECO TECH LABORATORY LTD. | ICP CERTIFICATE OF ANALYSIS AS 2007-5680 | Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10102	1.7	0.83	<5	70	<5	2.89	3	14	83	1612	4.21	<10	0.84	1149	16	0.02	6	1370	30	15	<20	165	0.04	<10	32	<10	4	90
27	X10103	<0.2	1.10	<5	285	15	0.59	<1	7	113	8	2.25	<10	0.64	546	2	0.12	6	940	30	10	<20	105	0.11	<10	48	<10	2	43
28	X10104	3.8	1.15	50	65	<5	0.78	4	18	59	3381	4.15	20	0.57	290	213	0.03	13	430	148	40	<20	40	0.03	<10	46	<10	6	169
29	X10105	1.9	0.85	5	40	<5	1.89	3	12	83	1831	3.44	<10	0.86	676	22	0.02	6	1420	28	10	<20	123	0.02	<10	26	<10	3	129
30	X10106	2.2	0.65	<5	35	<5	2.30	2	13	72	2201	3.40	<10	0.82	1151	18	0.01	6	1360	32	10	<20	77	0.02	<10	21	<10	4	86
31	X10107	8.4	0.19	20	45	<5	2.13	3	13	165	5457	3.75	<10	0.49	1028	11	<0.01	6	240	54	20	<20	73	0.02	<10	5	<10	1	75
32	X10108	>30	0.17	140	45	<5	1.29	10	21	136	6000	7.01	<10	0.41	769	14	<0.01	9	140	126	145	<20	42	0.02	<10	13	<10	<1	369
33	X10109	5.9	0.40	<5	35	<5	1.72	4	14	91	3381	4.74	<10	0.51	974	17	<0.01	9	1100	76	20	<20	61	<0.01	<10	17	<10	3	80
34	X10110	2.2	0.87	<5	45	<5	2.05	2	12	90	1943	4.19	<10	0.93	1043	15	0.02	5	1260	40	10	<20	82	0.03	<10	36	<10	2	81
35	X10111	2.4	0.88	<5	50	<5	2.35	2	14	92	2252	3.74	<10	0.90	1301	24	0.01	5	1240	50	10	<20	96	0.03	<10	27	<10	3	77
QC DATA:																													
Repeat:																													
1	X10077	1.9	1.29	<5	60	<5	2.37	2	17	67	1308	4.27	<10	1.20	697	80	0.05	7	1350	36	20	<20	122	0.06	<10	77	<10	3	71
10	X10086	1.8	0.62	<5	70	<5	3.09	2	10	67	1383	3.02	<10	0.75	1177	21	0.01	3	1350	26	5	<20	158	0.02	<10	20	<10	5	75
19	X10095	3.9	0.44	<5	50	<5	2.40	2	13	90	2632	4.02	<10	0.73	1423	14	<0.01	7	1250	40	5	<20	106	0.03	<10	15	<10	5	44
Resplit:																													
1	X10077	1.9	1.29	<5	65	<5	2.21	3	18	53	1409	4.13	<10	1.19	677	79	0.05	6	1480	40	20	<20	140	0.06	<10	70	<10	4	72
Standard:																													
PB113A		11.5	0.26	45	55	<5	1.68	38	3	6	2307	1.06	<10	0.10	1425	68	0.02	2	90	5410	15	<20	88	0.02	<10	7	<10	<1	6996

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5680S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5681

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07181
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	X10147	1.00	0.029		
2	X10148	1.99	0.058	32.5	0.948
3	X10149	0.31	0.009		
4	X10150	1.57	0.046		
5	X10151	4.96	0.145		
6	X10152	<0.03	<0.001		
7	X10153	1.64	0.048		
8	X10154	2.23	0.065		
9	X10155	2.07	0.060		
10	X10156	1.44	0.042		
11	X10157	1.30	0.038		
12	X10158	1.05	0.031		
13	X10159	1.19	0.035		
14	X10160	1.40	0.041		
15	X10161	1.12	0.033		
16	X10162	1.24	0.036		
17	X10163	1.31	0.038		
18	X10164	1.74	0.051		
19	X10165	1.52	0.044		
20	X10166	1.37	0.040		
21	X10167	1.23	0.036		
22	X10168	1.41	0.041		
23	X10169	1.23	0.036		
24	X10170	1.04	0.030		
25	X10171	1.39	0.041		
26	X10172	1.16	0.034		
27	X10173	2.68	0.078		
28	X10174	1.83	0.053		
29	X10175	1.26	0.037		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5681 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X10176	1.76	0.051
31	X10177	1.61	0.047
32	X10178	1.59	0.046
33	X10179	0.95	0.028
34	X10180	1.57	0.046
35	X10181	1.11	0.032

QC DATA:

Repeat:

1	X10147	1.02	0.030
2	X10148	1.89	0.055
4	X10150	1.68	0.049
5	X10151	4.90	0.143
10	X10156	1.41	0.041
19	X10165	1.61	0.047
27	X10173	2.73	0.080

Resplits:

1	X10147	0.96	0.028

Standard:

OXK48		3.53	0.103

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 2007-5681

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07181
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10147	4.8	0.38	20	50	<5	1.64	5	12	96	2395	3.82	<10	0.30	879	28	<0.01	4	1040	120	10	<20	77	0.02	<10	16	<10	3	282
2	X10148	>30	0.34	100	55	<5	0.91	6	15	94	4649	6.39	<10	0.14	506	16	<0.01	11	790	30	160	<20	45	0.01	<10	12	<10	<1	125
3	X10149	3.2	1.23	45	70	<5	0.97	3	21	65	2590	3.46	20	0.60	187	217	0.04	9	490	72	20	<20	55	0.04	<10	48	<10	8	276
4	X10150	6.4	0.43	15	45	<5	1.27	3	15	98	3960	5.26	<10	0.24	662	19	<0.01	9	760	58	15	<20	66	<0.01	<10	16	<10	<1	37
5	X10151	5.8	0.43	25	45	<5	1.52	2	14	106	4041	3.84	<10	0.33	691	26	<0.01	9	880	34	20	<20	69	0.03	<10	14	<10	3	44
6	X10152	<0.2	1.03	25	265	25	0.62	<1	7	91	9	2.20	10	0.58	538	2	0.11	7	980	20	<5	<20	93	0.11	<10	48	<10	6	50
7	X10153	4.4	0.39	10	50	<5	1.76	5	11	123	3800	4.48	<10	0.37	669	18	0.01	9	860	82	20	<20	189	<0.01	<10	22	<10	2	195
8	X10154	3.8	0.43	10	50	<5	1.64	6	12	97	3429	3.90	<10	0.36	803	22	<0.01	10	870	192	20	<20	97	<0.01	<10	15	<10	3	270
9	X10155	4.9	0.55	10	55	<5	1.43	3	12	133	4243	4.33	<10	0.36	752	17	<0.01	9	720	68	15	<20	73	<0.01	<10	15	<10	2	100
10	X10156	5.4	0.40	20	45	<5	1.23	3	11	108	4104	3.93	<10	0.29	549	16	<0.01	7	850	58	10	<20	55	<0.01	<10	13	<10	2	90
11	X10157	3.8	0.60	20	50	<5	1.29	2	14	127	3649	4.36	<10	0.40	835	17	<0.01	9	790	36	15	<20	67	<0.01	<10	17	<10	2	68
12	X10158	3.7	0.70	15	50	<5	1.06	3	15	91	2955	4.45	<10	0.22	431	19	<0.01	9	1190	60	15	<20	54	<0.01	<10	15	<10	2	87
13	X10159	3.8	0.88	15	75	<5	2.07	3	11	95	2750	3.99	<10	0.62	1014	20	<0.01	8	1050	66	25	<20	118	0.01	<10	27	<10	3	130
14	X10160	4.2	0.49	20	45	<5	1.78	2	16	107	3198	3.77	<10	0.48	830	17	<0.01	6	820	68	15	<20	100	<0.01	<10	19	<10	2	67
15	X10161	4.0	0.40	<5	40	<5	0.88	2	17	135	2946	4.28	<10	0.20	340	24	0.01	7	680	62	<5	<20	88	<0.01	<10	15	<10	<1	33
16	X10162	4.4	0.37	10	60	<5	1.08	3	16	105	3390	4.91	<10	0.40	552	14	0.01	7	670	60	10	<20	232	0.01	<10	16	<10	2	91
17	X10163	4.7	0.49	<5	50	<5	0.98	5	15	101	3677	5.24	<10	0.39	777	14	<0.01	10	650	84	20	<20	43	0.01	<10	20	<10	<1	196
18	X10164	6.1	0.38	15	50	<5	1.31	12	15	114	5012	4.71	<10	0.29	489	38	<0.01	9	780	214	15	<20	95	<0.01	<10	15	<10	2	716
19	X10165	3.7	0.54	<5	55	<5	1.71	4	14	120	3018	4.75	<10	0.51	704	18	0.01	10	740	44	15	<20	152	<0.01	<10	27	<10	1	105
20	X10166	3.1	0.73	15	50	<5	1.05	2	12	81	2574	4.19	<10	0.61	558	18	<0.01	7	980	42	25	<20	48	0.01	<10	25	<10	3	80
21	X10167	4.2	0.43	10	40	<5	1.13	8	12	141	2894	4.34	<10	0.27	694	17	0.01	9	750	162	20	<20	39	0.01	<10	16	<10	3	357
22	X10168	4.6	0.27	5	45	<5	0.88	1	14	176	4468	4.02	<10	0.26	535	14	0.01	7	270	40	<5	<20	33	<0.01	<10	14	<10	<1	39
23	X10169	2.9	0.59	10	50	<5	1.04	2	15	124	2767	4.79	<10	0.45	703	14	<0.01	9	630	62	20	<20	37	0.01	<10	27	<10	1	84
24	X10170	5.9	0.36	<5	55	<5	0.81	15	13	134	3559	5.28	<10	0.23	635	20	<0.01	11	590	754	20	<20	37	<0.01	<10	19	<10	<1	934
25	X10171	3.6	0.50	15	40	<5	0.59	2	12	145	2500	4.07	<10	0.32	487	12	<0.01	6	580	88	<5	<20	35	0.01	<10	19	<10	<1	129

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10172	3.8	0.88	10	50	<5	0.90	8	16	91	2476	4.86	<10	0.65	710	20	<0.01	8	950	130	25	<20	111	0.01	<10	30	<10	1	273
27	X10173	3.6	0.71	10	55	<5	0.95	2	14	129	3654	4.30	<10	0.46	575	21	<0.01	8	560	36	15	<20	50	<0.01	<10	30	<10	1	73
28	X10174	3.9	0.67	<5	50	<5	1.47	2	13	98	3502	4.81	<10	0.45	592	15	<0.01	7	780	36	10	<20	88	<0.01	<10	32	<10	<1	63
29	X10175	3.2	0.78	25	60	<5	0.97	4	10	105	2010	5.18	<10	0.52	521	19	<0.01	10	940	38	30	<20	64	0.01	<10	35	<10	1	66
30	X10176	3.5	0.69	20	60	<5	0.79	3	14	111	3036	5.32	<10	0.47	406	21	0.01	10	880	46	20	<20	64	0.01	<10	36	<10	2	70
31	X10177	3.1	0.75	5	65	<5	0.77	2	10	107	2608	4.39	<10	0.53	331	16	0.01	7	860	30	15	<20	51	0.01	<10	39	<10	1	59
32	X10178	4.0	0.58	30	45	<5	1.19	3	14	133	3205	4.97	<10	0.39	557	15	<0.01	9	660	64	10	<20	49	<0.01	<10	24	<10	<1	105
33	X10179	3.0	0.87	15	40	<5	1.36	2	10	83	2474	4.34	<10	0.65	603	17	<0.01	7	920	42	15	<20	62	<0.01	<10	28	<10	<1	78
34	X10180	4.0	0.64	5	50	<5	1.31	3	12	99	2918	4.71	<10	0.45	449	17	<0.01	9	710	100	15	<20	123	<0.01	<10	25	<10	<1	132
35	X10181	3.4	0.72	<5	50	<5	1.11	3	12	107	3049	4.38	<10	0.60	603	19	<0.01	9	700	38	25	<20	62	<0.01	<10	25	<10	1	59
QC DATA:																													
Repeat:																													
1	X10147	5.0	0.37	20	40	<5	1.65	5	12	94	2414	3.82	<10	0.30	885	28	<0.01	7	940	114	10	<20	74	0.02	<10	16	<10	2	279
10	X10156	5.3	0.37	25	50	<5	1.21	5	11	103	4085	3.87	<10	0.29	541	18	<0.01	11	810	56	15	<20	58	<0.01	<10	13	<10	2	88
19	X10165	3.5	0.52	10	50	<5	1.67	3	14	113	2989	4.61	<10	0.50	685	16	0.01	8	780	46	15	<20	145	0.02	<10	26	<10	2	102
Resplit:																													
1	X10147	4.9	0.35	10	40	<5	1.77	6	13	105	2442	3.79	<10	0.30	899	20	<0.01	8	930	102	15	<20	81	0.01	<10	14	<10	2	266
Standard:																													
Pb113A		11.8	0.28	60	80	<5	1.71	41	2	7	2304	1.07	<10	0.11	1445	71	0.02	5	90	5526	40	<20	101	<0.01	<10	9	<10	<1	7149

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5679
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5682

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

29-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07178
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05518	0.23	0.007
2	X05519	0.31	0.009
3	X05520	0.28	0.008
4	X05521	0.30	0.009
5	X05522	0.19	0.006
6	X05523	0.27	0.008
7	X05524	0.34	0.010
8	X05525	0.48	0.014
9	X05526	0.34	0.010
10	X05527	0.39	0.011
11	X05528	0.35	0.010
12	X05529	0.41	0.012
13	X05530	0.47	0.014
14	X05531	0.44	0.013
15	X05532	0.50	0.015
16	X05533	0.33	0.010
17	X05534	0.32	0.009
18	X05535	0.44	0.013
19	X05536	0.40	0.012
20	X05537	0.30	0.009
21	X05538	0.38	0.011
22	X05539	0.34	0.010
23	X05540	1.45	0.042
24	X05541	<0.03	<0.001
25	X05542	0.52	0.015
26	X05543	0.47	0.014
27	X05544	0.57	0.017
28	X05545	0.21	0.006
29	X05546	0.30	0.009

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5682 29-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X05547	0.21	0.006
31	X05548	0.28	0.008
32	X05549	0.59	0.017
33	X05550	0.15	0.004
34	X05551	0.23	0.007
35	X05552	0.20	0.006

QC DATA:

Repeat:

1	X05518	0.22	0.006
10	X05527	0.42	0.012
19	X05536	0.32	0.009

Resplits:

1	X05518	0.20	0.006

Standard:

OXK48		3.51	0.102

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

29-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5682

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07178
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05518	0.4	0.68	<5	30	<5	1.09	2	16	107	690	4.57	<10	0.85	859	67	0.01	18	980	36	10	<20	27	0.02	<10	10	<10	<1	28
2	X05519	0.9	1.68	<5	40	<5	1.25	1	18	83	964	4.53	<10	2.26	1094	47	0.01	19	820	38	20	<20	27	0.02	<10	28	<10	2	50
3	X05520	0.4	1.74	<5	45	<5	0.88	<1	13	99	646	3.61	<10	2.14	627	58	0.01	16	1200	42	15	<20	25	0.02	<10	35	<10	3	78
4	X05521	0.7	0.93	<5	40	<5	1.14	2	17	94	958	4.52	<10	1.14	746	96	0.01	14	640	50	15	<20	32	0.02	<10	15	<10	<1	57
5	X05522	3.4	0.73	25	35	<5	0.84	2	15	92	929	4.18	<10	0.85	617	49	0.01	13	850	68	60	<20	31	0.02	<10	10	<10	<1	58
6	X05523	0.7	1.41	<5	35	<5	1.06	<1	11	79	727	3.37	<10	1.75	834	53	0.01	12	1160	48	10	<20	45	0.02	<10	22	<10	3	58
7	X05524	1.2	0.64	<5	40	<5	1.64	2	21	99	1258	6.50	<10	0.72	1033	35	0.01	23	700	116	5	<20	43	0.02	<10	8	<10	<1	36
8	X05525	1.7	2.12	5	55	<5	3.81	1	12	108	669	3.87	<10	2.36	1229	134	<0.01	14	1010	52	20	<20	62	0.02	<10	53	<10	3	96
9	X05526	1.2	1.55	<5	50	<5	2.03	2	22	92	943	5.37	<10	1.65	689	68	<0.01	21	890	42	15	<20	52	0.02	<10	27	<10	1	51
10	X05527	1.4	0.79	<5	50	<5	1.82	2	16	114	970	4.64	<10	0.74	667	73	<0.01	19	730	56	10	<20	54	0.02	<10	11	<10	1	42
11	X05528	2.1	1.11	10	40	<5	2.49	2	17	68	784	4.97	<10	1.23	1163	102	0.01	28	980	44	25	<20	58	0.02	<10	22	<10	<1	67
12	X05529	3.3	1.19	<5	60	<5	3.21	2	15	113	836	6.23	<10	1.48	1737	108	<0.01	11	1270	64	15	<20	62	0.03	<10	25	<10	<1	47
13	X05530	1.8	1.37	<5	35	<5	1.29	1	16	121	1790	5.19	<10	1.18	577	92	0.01	7	1110	32	10	<20	23	0.02	<10	25	<10	<1	46
14	X05531	1.4	1.46	<5	40	<5	1.21	2	18	63	1381	5.61	<10	1.11	561	40	<0.01	7	1380	42	5	<20	26	0.02	<10	22	<10	<1	61
15	X05532	1.3	1.54	<5	50	<5	1.34	1	17	86	1475	5.32	<10	1.13	619	58	0.01	7	1250	42	5	<20	29	0.02	<10	23	<10	<1	52
16	X05533	0.9	1.41	<5	55	<5	1.92	1	14	94	767	4.10	<10	1.44	651	76	0.01	11	940	62	10	<20	53	0.02	<10	25	<10	4	50
17	X05534	0.9	1.15	<5	40	<5	1.65	1	12	125	720	3.60	<10	1.16	550	77	0.01	12	750	50	10	<20	33	0.01	<10	24	<10	1	66
18	X05535	0.7	1.48	10	70	20	2.77	<1	12	94	814	2.91	<10	1.63	819	55	0.01	11	800	52	<5	<20	73	0.03	<10	27	<10	6	41
19	X05536	1.0	1.55	10	40	<5	2.33	2	10	98	721	3.46	<10	1.81	686	58	0.01	13	890	44	25	<20	46	0.01	<10	30	<10	2	75
20	X05537	0.5	1.41	<5	45	<5	5.75	1	13	70	506	3.25	<10	1.67	1824	56	<0.01	16	1030	40	20	<20	83	0.02	<10	28	<10	4	53
21	X05538	1.1	1.16	<5	45	<5	1.56	1	18	104	1075	4.43	<10	1.08	549	67	0.01	18	590	44	5	<20	37	0.02	<10	18	<10	<1	33
22	X05539	0.9	1.44	<5	45	<5	1.28	3	16	104	969	5.02	<10	1.28	514	112	0.01	19	530	38	30	<20	40	0.01	<10	19	<10	<1	36
23	X05540	<0.2	1.00	1465	125	20	0.01	14	8	42	40	4.84	20	0.02	101	6	0.03	16	230	46	95	<20	21	0.03	<10	17	<10	3	50
24	X05541	<0.2	1.07	10	265	30	0.60	<1	8	151	7	2.49	<10	0.66	589	2	0.14	7	930	28	<5	<20	91	0.13	<10	51	<10	6	44
25	X05542	1.0	1.52	<5	55	<5	1.51	2	15	105	1172	4.18	<10	1.12	552	96	0.01	14	410	34	15	<20	42	0.02	<10	15	<10	<1	60

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05543	0.9	1.38	<5	45	<5	1.07	1	17	107	1138	3.97	<10	1.11	462	71	0.01	18	750	46	10	<20	30	0.01	<10	16	<10	<1	50
27	X05544	1.0	1.13	<5	30	<5	1.28	<1	18	134	1448	4.38	<10	0.89	456	65	0.01	14	770	60	<5	<20	28	0.02	<10	14	<10	<1	42
28	X05545	0.8	0.96	<5	40	<5	1.33	<1	13	94	887	3.50	<10	0.78	488	48	0.02	12	600	52	<5	<20	37	0.01	<10	14	<10	1	50
29	X05546	0.7	1.76	<5	60	<5	2.48	1	20	96	816	4.62	<10	1.74	830	71	0.02	27	1490	58	10	<20	57	0.02	<10	39	<10	6	74
30	X05547	1.0	0.96	5	40	<5	2.33	1	14	84	630	4.28	<10	0.74	626	43	0.01	10	1490	42	<5	<20	57	0.02	<10	19	<10	5	37
31	X05548	0.9	1.35	<5	40	<5	1.72	1	18	97	937	4.62	<10	1.14	509	137	0.01	5	1520	52	<5	<20	38	0.02	<10	27	<10	3	62
32	X05549	1.1	1.24	<5	50	<5	2.31	2	19	77	926	5.30	<10	1.10	775	78	0.02	6	1380	66	15	<20	56	0.02	<10	24	<10	4	72
33	X05550	0.7	0.92	<5	45	<5	1.96	2	16	83	718	4.15	<10	0.67	546	51	0.02	7	1610	40	25	<20	71	<0.01	<10	21	<10	4	39
34	X05551	0.4	1.35	<5	50	<5	1.24	1	14	78	671	4.07	<10	1.17	372	71	0.02	4	1630	42	10	<20	46	0.02	<10	34	<10	5	40
35	X05552	0.6	1.24	<5	55	<5	1.64	1	19	93	688	5.36	<10	1.09	365	83	0.02	5	1500	42	10	<20	58	0.02	<10	36	<10	4	26
QC DATA:																													
Repeat:																													
1	X05518	0.6	0.73	<5	45	<5	1.14	1	17	115	708	4.71	<10	0.88	885	70	0.01	18	1010	42	5	<20	40	0.02	<10	11	<10	1	30
10	X05527	1.4	0.83	<5	35	<5	1.81	2	15	115	962	4.61	<10	0.75	663	74	<0.01	19	720	54	10	<20	26	0.01	<10	12	<10	<1	43
19	X05536	0.9	1.64	20	50	<5	2.37	1	11	90	738	3.51	<10	1.87	701	60	0.02	11	930	54	20	<20	61	0.02	<10	30	<10	4	76
Resplit:																													
1	X05518	0.6	0.60	<5	35	<5	1.04	2	15	94	711	4.33	<10	0.76	835	60	0.01	18	960	36	10	<20	32	0.02	<10	9	<10	<1	27
Standard:																													
PB113A		11.1	0.32	45	70	<5	1.69	39	3	6	2267	1.16	<10	0.11	1515	67	0.02	2	100	5640	25	<20	86	0.02	<10	8	<10	<1	6932

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5682S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5683

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07180
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	X10112	1.19	0.035		
2	X10113	1.08	0.031		
3	X10114	0.99	0.029		
4	X10115	0.59	0.017		
5	X10116	0.58	0.017		
6	X10117	0.52	0.015		
7	X10118	0.88	0.026		
8	X10119	0.69	0.020		
9	X10120	0.48	0.014		
10	X10121	0.56	0.016		
11	X10122	1.83	0.053		
12	X10123	0.50	0.015		
13	X10124	0.41	0.012		
14	X10125	0.45	0.013		
15	X10126	0.54	0.016	34.5	1.01
16	X10127	0.53	0.015	47.5	1.39
17	X10128	0.71	0.021		
18	X10129	0.73	0.021		
19	X10130	0.73	0.021		
20	X10131	0.56	0.016		
21	X10132	1.57	0.046		
22	X10133	0.70	0.020		
23	X10134	0.75	0.022		
24	X10135	0.55	0.016		
25	X10136	0.45	0.013		
26	X10137	0.49	0.014		
27	X10138	0.54	0.016		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5683 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
28	X10139	0.57	0.017	87.0	2.54
29	X10140	0.66	0.019	33.2	0.97
30	X10141	1.02	0.030		
31	X10142	0.69	0.020		
32	X10143	0.69	0.020		
33	X10144	0.93	0.027		
34	X10145	<0.03	<0.001		
35	X10146	1.30	0.038		
QC DATA:					
Repeat:					
1	X10112	1.19	0.035		
10	X10121	0.54	0.016		
15	X10126			33.2	0.97
19	X10130	0.75	0.022		
Resplits:					
1	X10112	1.22	0.036		
Standard:					
OXK48		3.52	0.103		
Pb113				22.6	0.66

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 2007-5683

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07180
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10112	3.4	1.03	<5	55	<5	1.79	3	20	68	3921	5.44	<10	0.90	939	15	0.02	8	1220	30	20	<20	89	0.01	<10	44	<10	1	95
2	X10113	4.6	0.80	<5	60	<5	0.86	4	21	101	4712	7.22	<10	0.72	621	15	0.02	12	460	60	25	<20	39	0.01	<10	42	<10	<1	80
3	X10114	3.7	0.99	<5	50	<5	0.71	2	15	114	4262	4.78	<10	0.96	824	19	0.03	9	680	30	20	<20	43	<0.01	<10	49	<10	1	89
4	X10115	2.1	1.13	<5	50	<5	1.44	3	13	74	1869	4.61	<10	1.02	1131	27	0.04	8	1220	30	20	<20	77	0.02	<10	55	<10	2	167
5	X10116	2.3	1.03	<5	55	<5	1.83	4	14	99	2046	4.56	<10	1.00	1302	26	0.04	10	1210	36	25	<20	99	0.02	<10	61	<10	2	166
6	X10117	2.3	1.15	<5	55	<5	1.88	2	13	66	1893	4.16	<10	1.05	1261	29	0.04	7	1230	40	20	<20	103	0.02	<10	54	<10	3	144
7	X10118	3.0	1.29	<5	50	<5	1.72	3	15	82	2960	4.85	<10	1.32	1374	25	0.03	8	1060	46	25	<20	118	0.02	<10	53	<10	5	136
8	X10119	2.1	1.01	<5	45	<5	1.78	2	14	92	2422	3.97	<10	1.05	1412	23	0.01	7	1060	42	15	<20	56	0.02	<10	34	<10	3	107
9	X10120	3.8	0.35	5	50	<5	1.62	4	18	110	3673	5.77	<10	0.32	856	21	<0.01	9	760	56	10	<20	43	0.01	<10	17	<10	1	93
10	X10121	4.1	0.85	<5	45	<5	3.20	5	12	78	1940	4.64	<10	1.26	1955	25	<0.01	9	1230	62	30	<20	74	0.04	<10	25	<10	4	127
11	X10122	4.0	1.16	35	55	<5	1.03	4	22	63	8736	4.15	20	0.64	205	634	0.05	69	30	74	55	<20	58	<0.01	<10	46	<10	7	77
12	X10123	3.8	0.57	<5	55	<5	2.34	2	12	71	2139	3.52	<10	0.72	1422	29	<0.01	6	1170	28	10	<20	86	0.02	<10	21	<10	5	68
13	X10124	8.1	0.39	10	50	<5	1.48	9	14	90	2282	5.65	<10	0.23	985	19	<0.01	12	1050	120	30	<20	69	0.02	<10	17	<10	<1	454
14	X10125	4.7	0.38	35	45	<5	2.38	4	15	106	2384	4.11	<10	0.57	1927	25	<0.01	8	1060	38	20	<20	96	0.02	<10	18	<10	4	148
15	X10126	>30	0.46	80	40	<5	2.81	23	15	94	3191	4.23	<10	0.63	2345	25	<0.01	8	1090	624	160	<20	153	0.02	<10	17	<10	4	1528
16	X10127	>30	0.41	105	35	<5	2.64	29	15	91	2974	4.30	<10	0.66	2584	26	<0.01	7	1090	842	240	<20	161	0.02	<10	16	<10	3	1822
17	X10128	21.7	0.46	40	45	<5	1.73	15	15	125	2949	5.02	<10	0.38	1293	28	<0.01	11	1220	336	80	<20	94	0.02	<10	16	<10	2	865
18	X10129	3.5	0.64	<5	50	<5	2.54	<1	11	90	2356	3.04	<10	0.53	1076	23	<0.01	3	960	44	<5	<20	241	0.02	<10	13	<10	6	77
19	X10130	2.8	0.62	<5	50	<5	1.07	2	14	85	2607	4.39	<10	0.50	787	25	0.02	8	820	80	10	<20	79	<0.01	<10	21	<10	2	58
20	X10131	2.3	0.77	<5	35	<5	0.80	9	12	79	1941	4.30	<10	0.69	893	29	0.01	7	990	228	15	<20	54	0.01	<10	21	<10	3	278
21	X10132	3.8	1.18	<5	50	<5	0.86	2	18	73	3320	5.02	<10	1.06	1028	28	0.02	8	910	56	25	<20	66	0.01	<10	33	<10	2	95
22	X10133	2.1	0.98	<5	45	<5	1.38	3	11	67	1846	3.91	<10	1.14	1396	21	0.02	9	1010	62	40	<20	76	0.01	<10	27	<10	4	89
23	X10134	2.3	1.06	<5	45	<5	1.43	3	13	87	2163	4.28	<10	1.15	1189	17	0.02	9	1130	44	30	<20	107	0.02	<10	35	<10	4	90
24	X10135	2.1	0.56	5	45	<5	2.39	3	15	113	1986	3.85	<10	0.72	1502	21	<0.01	9	1040	40	25	<20	174	0.02	<10	25	<10	3	55
25	X10136	3.4	0.36	<5	50	<5	2.48	3	13	111	2555	4.16	<10	0.58	1341	12	0.01	8	740	50	15	<20	243	0.02	<10	19	<10	3	69

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10137	2.4	0.57	<5	60	<5	2.64	1	11	137	1793	3.68	<10	0.86	1544	21	0.01	7	880	32	15	<20	174	0.02	<10	24	<10	4	70
27	X10138	14.1	0.33	25	45	<5	2.63	6	15	113	3522	4.96	<10	0.74	2149	12	<0.01	8	760	102	20	<20	190	0.02	<10	15	<10	3	149
28	X10139	>30	0.29	85	50	<5	0.89	7	12	125	2804	4.81	<10	0.19	842	15	<0.01	10	880	368	95	<20	91	0.01	<10	12	<10	2	316
29	X10140	>30	0.37	205	40	<5	1.08	8	14	132	2809	5.03	<10	0.21	1044	17	<0.01	9	1010	236	170	<20	96	0.02	<10	13	<10	2	271
30	X10141	11.4	0.29	30	55	<5	0.47	5	12	127	3228	6.18	<10	0.04	279	16	<0.01	11	950	72	25	<20	43	0.01	<10	12	<10	1	122
31	X10142	19.2	0.43	75	45	<5	1.19	3	14	180	4158	4.49	<10	0.20	665	10	0.01	8	520	70	45	<20	122	<0.01	<10	13	<10	1	132
32	X10143	5.7	0.85	15	45	<5	1.11	3	14	102	2674	4.47	<10	0.74	1012	17	0.01	9	1060	48	20	<20	100	0.01	<10	22	<10	3	89
33	X10144	4.0	0.84	<5	55	<5	1.72	4	15	106	2597	4.48	<10	0.77	1106	24	0.01	13	1040	48	40	<20	134	0.02	<10	32	<10	2	77
34	X10145	<0.2	1.14	5	280	25	0.69	<1	7	95	7	2.31	<10	0.64	576	4	0.12	8	980	26	15	<20	92	0.10	<10	51	<10	5	49
35	X10146	4.3	0.38	<5	35	<5	2.29	2	12	123	3515	3.90	<10	0.45	879	20	0.01	6	780	40	<5	<20	513	0.02	<10	20	<10	2	65
QC DATA:																													
Repeat:																													
1	X10112	3.5	1.10	<5	55	<5	1.79	4	21	72	4043	5.45	<10	0.93	944	16	0.02	10	1250	36	30	<20	100	0.01	<10	46	<10	4	94
10	X10121	4.1	0.95	<5	55	<5	3.24	5	13	85	2018	4.71	<10	1.31	1988	33	<0.01	11	1230	70	40	<20	89	0.02	<10	28	<10	4	130
19	X10130	2.9	0.67	<5	45	<5	1.07	2	14	91	2573	4.39	<10	0.50	787	27	0.02	8	850	82	15	<20	81	0.01	<10	22	<10	3	57
Resplit:																													
1	X10112	3.7	1.13	<5	50	<5	1.70	5	21	88	4192	5.52	<10	0.97	916	16	0.02	14	1230	34	35	<20	101	<0.01	<10	48	<10	2	94
Standard:																													
PB113A		11.2	0.24	45	70	<5	1.77	36	2	6	2233	1.12	<10	0.14	1521	71	0.02	7	90	5642	20	<20	85	<0.01	<10	11	<10	<1	7126

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5683
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5684

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07182
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10182	0.65	0.019
2	X10183	0.79	0.023
3	X10184	1.01	0.029
4	X10185	0.94	0.027
5	X10186	1.25	0.036
6	X10187	2.03	0.059
7	X10188	1.50	0.044
8	X10189	1.14	0.033
9	X10190	1.31	0.038
10	X10191	0.79	0.023
11	X10192	0.96	0.028
12	X10193	0.89	0.026
13	X10194	1.34	0.039
14	X10195	0.34	0.010
15	X10196	0.37	0.011
16	X10197	0.27	0.008
17	X10198	0.22	0.006
18	X10199	0.45	0.013
19	X10200	0.44	0.013
20	X10201	0.72	0.021
21	X10202	1.49	0.043
22	X10203	<0.03	<0.001
23	X10204	0.66	0.019
24	X10205	0.75	0.022
25	X10206	1.01	0.029
26	X10207	0.49	0.014
27	X10208	1.28	0.037
28	X10209	0.83	0.024
29	X10210	0.40	0.012

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5684 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X10211	0.27	0.008
31	X10212	0.23	0.007
32	X10213	0.28	0.008
33	X10214	0.39	0.011
34	X10215	0.38	0.011
35	X10216	0.44	0.013

QC DATA:

Repeat:

1	X10182	0.71	0.021
2	X10183	0.86	0.025
6	X10186	2.09	0.061
10	X10191	0.90	0.026
19	X10200	0.44	0.013
24	X10205	0.80	0.023
26	X10207	0.51	0.015
27	X10208	1.31	0.038
28	X10209	0.90	0.026
35	X10216	0.42	0.012

Resplits:

1	X10182	0.74	0.022

Standard:

OXK48		3.56	0.104

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5684

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07182
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10182	4.3	0.26	20	40	<5	1.36	2	13	141	3662	4.49	<10	0.22	736	12	<0.01	7	530	54	5	<20	61	0.01	<10	9	<10	<1	63
2	X10183	7.7	0.22	85	45	<5	0.42	5	14	144	4676	5.65	<10	<0.01	216	13	<0.01	8	410	112	50	<20	33	<0.01	<10	9	<10	<1	114
3	X10184	3.7	0.27	60	50	<5	0.91	3	13	121	2948	6.08	<10	0.10	659	13	<0.01	8	740	36	25	<20	54	0.02	<10	11	<10	<1	39
4	X10185	4.5	0.30	145	50	<5	0.79	6	15	156	3587	5.85	<10	0.13	513	15	<0.01	12	760	52	35	<20	51	<0.01	<10	11	<10	<1	92
5	X10186	4.4	0.24	15	50	<5	0.90	8	13	127	3850	6.18	<10	0.06	641	17	<0.01	8	490	356	5	<20	75	0.01	<10	11	<10	<1	586
6	X10187	4.4	0.30	25	50	<5	0.89	2	13	153	3997	6.07	<10	0.02	579	15	<0.01	8	750	34	<5	<20	73	0.01	<10	13	<10	<1	15
7	X10188	4.7	0.45	35	50	<5	0.64	3	11	149	4596	5.50	<10	0.23	480	15	<0.01	10	580	34	15	<20	56	<0.01	<10	15	<10	<1	28
8	X10189	4.1	0.75	<5	55	<5	0.82	2	11	143	4162	4.71	<10	0.50	559	18	<0.01	9	570	38	20	<20	78	<0.01	<10	20	<10	<1	45
9	X10190	3.9	0.88	5	50	<5	0.80	2	10	170	3341	4.47	<10	0.60	550	20	<0.01	10	690	30	30	<20	68	0.01	<10	19	<10	1	50
10	X10191	3.0	0.66	<5	30	<5	1.38	2	10	136	2710	4.11	<10	0.80	1114	18	<0.01	7	890	26	10	<20	94	0.01	<10	16	<10	2	43
11	X10192	3.5	0.83	5	60	<5	1.14	3	12	112	2842	5.28	<10	0.84	855	17	<0.01	8	900	36	20	<20	88	0.01	<10	20	<10	2	50
12	X10193	4.8	0.27	80	45	<5	0.41	3	12	174	2639	5.35	<10	0.05	221	14	<0.01	9	570	44	30	<20	31	<0.01	<10	12	<10	<1	45
13	X10194	6.1	0.22	25	45	<5	0.49	6	15	207	3159	5.28	<10	0.04	310	34	<0.01	9	50	80	15	<20	53	<0.01	<10	31	<10	<1	217
14	X10195	6.3	0.16	<5	40	<5	0.19	4	17	185	3135	5.12	<10	0.01	154	37	<0.01	9	<10	94	20	<20	24	<0.01	<10	20	<10	<1	141
15	X10196	5.6	0.17	20	45	<5	0.21	3	10	188	2118	4.34	<10	0.05	169	16	<0.01	9	20	40	40	<20	31	<0.01	<10	25	<10	<1	47
16	X10197	7.0	0.17	35	55	<5	0.30	3	17	191	2404	5.99	<10	<0.01	223	36	<0.01	8	60	34	50	<20	34	0.01	<10	20	<10	<1	32
17	X10198	7.2	0.21	30	50	<5	0.35	4	19	202	2540	6.99	<10	0.01	244	40	<0.01	11	130	40	60	<20	29	0.01	<10	23	<10	<1	29
18	X10199	4.4	0.21	<5	45	<5	0.21	2	8	201	3304	4.47	<10	0.04	179	14	<0.01	8	20	60	<5	<20	36	<0.01	<10	28	<10	<1	42
19	X10200	3.8	0.17	<5	45	<5	0.14	6	12	220	2927	5.29	<10	0.05	155	24	<0.01	20	<10	62	55	<20	23	<0.01	<10	31	<10	<1	49
20	X10201	3.6	0.39	<5	55	<5	0.15	2	14	194	2505	5.79	<10	0.16	186	17	<0.01	5	80	58	<5	<20	35	0.01	<10	32	<10	<1	94
21	X10202	3.4	0.64	<5	45	<5	0.28	2	11	190	2177	5.02	<10	0.38	418	20	<0.01	11	110	26	20	<20	31	0.04	<10	45	<10	<1	87
22	X10203	<0.2	1.09	5	270	15	0.80	<1	7	90	8	2.32	10	0.68	565	2	0.12	6	910	32	5	<20	109	0.10	<10	51	<10	7	54
23	X10204	3.4	0.72	<5	60	<5	0.40	2	17	187	2596	5.45	<10	0.40	485	20	<0.01	8	210	72	15	<20	77	0.01	<10	45	<10	<1	81
24	X10205	3.0	0.81	20	50	<5	0.40	6	12	235	2605	5.58	<10	0.48	484	27	<0.01	22	180	72	80	<20	34	<0.01	<10	50	<10	<1	81
25	X10206	3.7	1.13	75	70	<5	0.76	3	18	69	3405	3.91	20	0.54	279	213	0.04	13	440	164	25	<20	36	0.05	<10	48	<10	8	169

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10207	2.7	0.46	<5	55	<5	0.36	4	11	192	1928	6.35	<10	0.21	362	25	<0.01	14	200	78	30	<20	46	<0.01	<10	38	<10	<1	53
27	X10208	3.2	0.66	<5	55	<5	0.80	3	11	186	2487	5.37	<10	0.38	637	19	<0.01	9	180	34	15	<20	86	0.01	<10	43	<10	<1	61
28	X10209	2.5	0.75	<5	45	<5	0.33	3	11	171	1879	5.73	<10	0.45	388	20	<0.01	10	290	48	25	<20	23	0.01	<10	42	<10	<1	101
29	X10210	3.4	0.28	<5	45	<5	0.24	2	10	258	2759	4.95	<10	0.10	208	16	<0.01	10	90	66	5	<20	41	0.01	<10	29	<10	<1	55
30	X10211	9.3	0.16	60	50	<5	0.16	6	13	191	5270	5.22	<10	<0.01	137	26	<0.01	8	<10	104	80	<20	32	<0.01	<10	14	<10	<1	213
31	X10212	11.5	0.12	65	45	<5	0.18	6	17	217	3778	5.80	<10	0.02	189	41	0.01	11	<10	78	140	<20	12	<0.01	<10	16	<10	<1	155
32	X10213	6.1	0.09	55	40	<5	0.16	6	11	216	2962	5.09	<10	<0.01	162	28	<0.01	9	<10	178	80	<20	12	<0.01	<10	12	<10	<1	277
33	X10214	8.0	0.19	90	55	<5	0.12	9	12	290	3607	6.19	<10	<0.01	114	29	<0.01	12	<10	106	85	<20	21	0.01	<10	38	<10	<1	360
34	X10215	8.3	0.11	20	50	<5	0.23	5	14	302	4261	6.23	<10	<0.01	217	19	<0.01	11	<10	128	45	<20	26	<0.01	<10	26	<10	<1	137
35	X10216	4.3	0.29	<5	60	<5	0.49	6	11	214	2237	6.72	<10	0.10	350	24	<0.01	12	<10	116	30	<20	42	0.01	<10	43	<10	<1	158
QC DATA:																													
Repeat:																													
1	X10182	4.1	0.31	15	40	<5	1.34	3	12	151	3632	4.42	<10	0.23	729	13	<0.01	9	550	54	10	<20	60	<0.01	<10	10	<10	<1	61
10	X10191	3.2	0.72	5	50	<5	1.34	2	11	141	2582	4.00	<10	0.77	1075	20	<0.01	7	880	32	25	<20	105	0.01	<10	18	<10	3	43
19	X10200	4.0	0.20	<5	50	<5	0.14	2	12	251	2996	5.34	<10	0.03	162	20	<0.01	19	<10	68	45	<20	26	<0.01	<10	36	<10	<1	53
Resplit:																													
1	X10182	4.5	0.50	20	50	<5	1.22	5	14	125	3705	5.03	<10	0.22	690	18	<0.01	10	580	58	10	<20	60	<0.01	<10	11	<10	<1	75
Standard:																													
Pb113		11.0	0.23	45	85	<5	1.68	35	2	7	2317	1.09	<10	0.15	1585	69	0.02	9	90	5614	20	<20	81	<0.01	<10	13	<10	<1	7036

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5679
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5685

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07183
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10217	0.67	0.020
2	X10218	0.50	0.015
3	X10219	1.30	0.038
4	X10220	0.41	0.012
5	X10221	0.31	0.009
6	X10222	0.39	0.011
7	X10223	0.65	0.019
8	X10224	1.16	0.034
9	X10225	0.74	0.022
10	X10226	1.10	0.032
11	X10227	0.66	0.019
12	X10228	0.40	0.012
13	X10229	0.88	0.026
14	X10230	1.02	0.030
15	X10231	0.87	0.025
16	X10232	1.02	0.030
17	X10233	0.94	0.027
18	X10234	1.31	0.038
19	X10235	1.01	0.029
20	X10236	1.69	0.049
21	X10237	1.83	0.053
22	X10238	1.24	0.036
23	X10239	0.68	0.020
24	X10240	0.70	0.020
25	X10241	0.75	0.022
26	X10242	<0.03	<0.001
27	X10243	0.60	0.017
28	X10244	0.54	0.016
29	X10245	1.37	0.040

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5685 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X10246	0.70	0.020
31	X10247	1.07	0.031
32	X10248	0.59	0.017
33	X10249	0.71	0.021
34	X10250	1.01	0.029
35	X10251	0.55	0.016

QC DATA:

Repeat:

1	X10217	0.72	0.021
10	X10226	1.18	0.034
19	X10235	0.99	0.029

Resplits:

1	X10217	0.65	0.019

Standard:

OXK48		3.52	0.103

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5685

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07183
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10217	4.4	0.23	<5	45	<5	0.33	3	16	176	4097	5.36	<10	0.13	298	27	<0.01	10	<10	54	15	<20	33	<0.01	<10	32	<10	<1	58
2	X10218	4.0	0.15	<5	45	<5	0.30	4	14	176	3123	4.85	<10	0.04	256	24	<0.01	8	<10	142	<5	<20	22	<0.01	<10	24	<10	<1	215
3	X10219	3.2	0.63	<5	50	<5	0.36	3	13	141	2146	6.65	<10	0.32	395	35	<0.01	8	200	68	10	<20	32	0.02	<10	44	<10	<1	103
4	X10220	3.1	0.27	<5	60	<5	0.20	4	20	154	1489	8.33	<10	0.05	168	23	<0.01	12	120	50	20	<20	27	0.01	<10	22	<10	<1	39
5	X10221	4.3	0.21	<5	50	<5	0.23	11	11	163	2284	6.36	<10	0.03	205	19	<0.01	9	120	332	10	<20	21	0.01	<10	40	<10	<1	563
6	X10222	4.1	0.18	<5	50	<5	0.21	6	12	184	3019	6.54	<10	0.02	195	27	<0.01	8	<10	164	<5	<20	23	<0.01	<10	31	<10	<1	282
7	X10223	3.4	0.40	<5	50	<5	0.47	7	12	169	2210	6.64	<10	0.17	485	19	<0.01	10	130	180	10	<20	29	0.01	<10	32	<10	<1	288
8	X10224	2.7	0.46	<5	50	<5	0.37	3	13	134	1648	6.61	<10	0.18	340	26	<0.01	7	260	70	5	<20	26	0.02	<10	29	<10	<1	75
9	X10225	4.8	0.24	<5	45	<5	0.21	4	11	202	2064	6.62	<10	<0.01	168	21	<0.01	11	150	102	10	<20	19	0.01	<10	28	<10	<1	47
10	X10226	2.9	0.43	<5	60	<5	0.39	3	12	157	2167	6.70	<10	0.21	355	23	<0.01	10	230	32	15	<20	35	0.01	<10	35	<10	<1	65
11	X10227	3.7	0.25	<5	55	<5	0.20	5	13	161	2380	6.98	<10	0.04	156	23	<0.01	14	160	56	30	<20	36	<0.01	<10	32	<10	<1	46
12	X10228	3.6	0.18	<5	60	<5	0.24	4	11	134	2192	6.78	<10	<0.01	169	20	<0.01	9	150	64	10	<20	37	0.01	<10	23	<10	<1	87
13	X10229	5.3	0.39	<5	65	<5	0.87	5	14	220	2627	7.13	<10	0.19	548	21	0.01	12	130	68	10	<20	63	0.02	<10	34	<10	<1	120
14	X10230	4.3	0.40	<5	55	<5	0.40	6	12	148	2563	6.48	<10	0.19	328	26	<0.01	10	120	46	10	<20	30	0.01	<10	37	<10	<1	163
15	X10231	3.4	0.48	<5	55	<5	0.87	1	11	236	2178	5.69	<10	0.23	592	15	0.01	9	120	30	<5	<20	58	0.01	<10	39	<10	<1	60
16	X10232	3.3	0.51	<5	55	<5	0.41	3	13	189	2174	6.93	<10	0.24	423	24	<0.01	9	220	32	10	<20	25	0.02	<10	45	<10	<1	57
17	X10233	4.2	0.46	<5	65	<5	0.39	2	13	189	2917	7.24	<10	0.18	344	28	<0.01	9	200	32	10	<20	39	0.02	<10	35	<10	<1	44
18	X10234	10.1	0.47	<5	70	<5	0.70	3	15	150	2607	7.67	<10	0.40	557	36	0.01	10	160	50	20	<20	58	0.02	<10	48	<10	<1	48
19	X10235	2.9	0.61	<5	55	<5	1.01	3	12	154	2066	6.60	<10	0.34	601	27	<0.01	10	410	78	20	<20	76	0.01	<10	33	<10	<1	99
20	X10236	3.4	0.37	<5	60	<5	0.53	3	16	166	2724	7.19	<10	0.13	388	30	<0.01	11	240	30	15	<20	35	0.03	<10	29	<10	<1	51
21	X10237	4.0	1.15	35	60	<5	1.01	3	22	64	8664	4.12	20	0.60	197	636	0.04	67	70	74	40	<20	56	<0.01	<10	45	<10	6	80
22	X10238	3.4	0.24	<5	50	<5	0.45	4	12	175	2601	5.65	<10	0.06	280	23	<0.01	11	40	28	10	<20	28	<0.01	<10	23	<10	<1	38
23	X10239	2.8	0.60	<5	55	<5	0.69	2	12	164	2299	7.16	<10	0.37	557	25	<0.01	8	210	28	5	<20	36	0.02	<10	34	<10	<1	73
24	X10240	3.1	0.52	<5	60	<5	0.39	4	14	143	2753	8.02	<10	0.29	320	27	<0.01	12	280	34	25	<20	30	0.01	<10	36	<10	<1	54
25	X10241	2.8	0.37	<5	55	<5	0.42	3	11	170	2514	5.86	<10	0.18	349	26	<0.01	11	100	18	15	<20	38	0.04	<10	34	<10	<1	31

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10242	<0.2	1.11	10	270	10	0.65	<1	7	96	11	2.26	10	0.62	560	2	0.13	4	920	14	<5	<20	99	0.10	<10	50	<10	6	48
27	X10243	2.5	0.51	<5	55	<5	0.38	4	13	163	1680	7.82	<10	0.21	290	25	0.01	13	280	22	20	<20	24	0.01	<10	34	<10	<1	40
28	X10244	3.3	0.30	<5	40	<5	0.17	2	11	150	2601	5.60	<10	0.11	165	42	<0.01	7	140	20	<5	<20	9	<0.01	<10	18	<10	<1	26
29	X10245	2.2	1.03	<5	60	<5	0.52	3	10	137	1067	6.61	<10	0.61	532	23	<0.01	9	570	30	15	<20	34	0.02	<10	44	<10	<1	78
30	X10246	3.5	0.41	<5	55	<5	0.27	3	12	180	2697	6.40	<10	0.16	230	25	<0.01	10	210	26	15	<20	28	<0.01	<10	26	<10	<1	45
31	X10247	3.9	0.35	<5	55	<5	0.68	3	12	150	2252	7.12	<10	0.10	358	25	0.01	10	240	62	10	<20	54	0.02	<10	36	<10	<1	29
32	X10248	4.4	0.28	<5	45	<5	0.93	4	11	193	3652	5.33	<10	0.09	349	24	0.01	8	190	56	<5	<20	67	0.01	<10	23	<10	<1	178
33	X10249	3.1	0.43	<5	50	<5	0.91	4	12	175	2688	5.63	<10	0.20	385	30	0.01	13	280	18	25	<20	56	<0.01	<10	36	<10	<1	35
34	X10250	3.4	0.39	<5	55	<5	1.06	2	10	158	2087	5.24	<10	0.23	439	26	0.01	6	310	20	5	<20	104	0.02	<10	41	<10	<1	41
35	X10251	4.3	0.44	<5	50	<5	0.94	11	12	175	2595	6.04	<10	0.27	485	25	0.01	11	340	108	15	<20	82	0.02	<10	42	<10	<1	589
QC DATA:																													
Repeat:																													
1	X10217	4.7	0.26	<5	50	<5	0.34	3	17	187	4268	5.70	<10	0.13	307	28	0.01	8	<10	52	10	<20	34	<0.01	<10	36	<10	<1	53
10	X10226	3.0	0.44	<5	55	<5	0.38	3	12	162	2085	6.67	<10	0.21	348	24	<0.01	10	220	30	15	<20	37	0.01	<10	38	<10	<1	65
19	X10235	2.8	0.69	<5	55	<5	1.02	4	12	165	2101	6.79	<10	0.37	617	29	<0.01	11	380	78	20	<20	82	0.02	<10	38	<10	<1	96
Resplit:																													
1	X10217	4.7	0.24	<5	50	<5	0.37	5	15	193	4220	5.42	<10	0.14	323	28	0.01	12	<10	50	15	<20	33	<0.01	<10	33	<10	<1	52
Standard:																													
Pb113a		11.6	0.26	50	60	<5	1.64	43	2	6	2284	1.10	<10	0.14	1469	60	0.02	8	90	5638	20	<20	81	<0.01	<10	11	<10	<1	7112

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5679
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5686

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07184
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10252	0.35	0.010
2	X10253	0.47	0.014
3	X10254	0.57	0.017
4	X10255	0.56	0.016
5	X10256	0.57	0.017
6	X10257	1.56	0.045
7	X10258	0.61	0.018
8	X10259	0.88	0.026
9	X10260	1.04	0.030
10	X10261	1.07	0.031
11	X10262	0.98	0.029
12	X10263	1.63	0.048
13	X10264	0.53	0.015
14	X10265	0.79	0.023
15	X10266	1.33	0.039
16	X10267	0.92	0.027
17	X10268	1.18	0.034
18	X10269	2.69	0.078
19	X10270	0.97	0.028
20	X10271	0.97	0.028
21	X10272	1.11	0.032
22	X10273	0.61	0.018
23	X10274	0.53	0.015
24	X10275	0.70	0.020
25	X10276	0.79	0.023
26	X10277	0.90	0.026
27	X10278	1.03	0.030
28	X10279	0.63	0.018
29	X10280	0.56	0.016

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5686 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X10281	1.14	0.033
31	X10282	<0.03	<0.001
32	X10283	0.29	0.008
33	X10284	1.01	0.029
34	X10285	0.97	0.028
35	X10286	0.71	0.021

QC DATA:

Repeat:

1	X10252	0.34	0.010
10	X10261	1.07	0.031
12	X10263	1.44	0.042
18	X10269	2.80	0.082
19	X10270	1.03	0.030

Resplits:

1	X10252	0.35	0.010

Standard:

OXK48		3.56	0.104

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5686

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1


No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07184
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10252	6.2	0.20	<5	55	<5	0.54	9	15	128	3113	7.28	<10	<0.01	297	84	<0.01	8	400	88	10	<20	39	0.02	<10	12	<10	<1	423
2	X10253	4.4	0.18	<5	50	<5	0.30	2	14	115	4321	6.28	<10	<0.01	124	50	<0.01	6	200	30	<5	<20	30	0.02	<10	13	<10	<1	20
3	X10254	5.8	0.17	<5	55	<5	0.72	3	15	144	7151	6.78	<10	<0.01	225	60	0.01	6	10	54	<5	<20	79	0.02	<10	16	<10	<1	86
4	X10255	3.9	0.21	<5	75	<5	0.68	5	19	106	3181	>10	<10	<0.01	203	53	0.01	9	570	54	10	<20	83	0.03	<10	20	<10	<1	95
5	X10256	3.9	0.19	<5	50	<5	0.23	3	12	182	2690	5.59	<10	<0.01	113	41	<0.01	7	210	52	5	<20	30	0.02	<10	14	<10	<1	43
6	X10257	3.7	0.47	<5	55	<5	0.70	2	11	209	2636	4.89	<10	0.19	394	26	<0.01	8	300	40	5	<20	51	0.02	<10	26	<10	<1	55
7	X10258	4.1	0.34	<5	60	<5	0.62	4	12	173	2352	6.77	<10	0.10	264	61	0.01	10	290	32	25	<20	77	0.02	<10	23	<10	<1	41
8	X10259	3.1	0.19	<5	65	<5	0.87	2	11	194	3213	4.49	<10	0.04	321	60	0.01	9	60	38	5	<20	125	0.01	<10	14	<10	<1	16
9	X10260	2.3	0.51	<5	55	<5	1.32	1	11	146	2168	4.75	<10	0.26	605	14	<0.01	5	300	20	<5	<20	81	0.02	<10	26	<10	<1	39
10	X10261	2.5	0.47	15	45	<5	0.70	7	9	143	1489	5.82	<10	0.16	387	36	0.01	7	650	34	15	<20	43	0.02	<10	15	<10	<1	225
11	X10262	4.1	0.32	<5	50	<5	0.47	3	12	186	3555	5.32	<10	0.10	326	40	0.01	7	210	78	<5	<20	43	0.02	<10	19	<10	<1	110
12	X10263	6.5	0.80	<5	180	<5	0.72	3	15	167	3487	6.93	<10	0.13	368	28	0.01	8	180	46	20	<20	63	0.03	<10	45	<10	<1	29
13	X10264	2.0	0.21	<5	60	<5	0.72	3	11	147	1569	5.80	<10	<0.01	352	29	<0.01	7	260	30	5	<20	56	0.02	<10	14	<10	<1	8
14	X10265	2.3	0.45	<5	45	<5	0.68	2	12	171	2237	4.78	<10	0.25	502	30	<0.01	7	320	30	10	<20	48	0.02	<10	21	<10	<1	45
15	X10266	2.7	0.63	<5	55	<5	0.68	2	10	136	2614	4.51	<10	0.45	480	13	<0.01	6	380	28	10	<20	58	0.02	<10	26	<10	<1	84
16	X10267	8.7	0.38	<5	45	<5	1.25	5	11	135	6440	5.46	<10	0.33	685	25	<0.01	6	30	50	15	<20	119	0.01	<10	21	<10	<1	59
17	X10268	4.4	0.38	<5	50	<5	1.14	3	12	147	3686	5.71	<10	0.17	360	28	<0.01	8	250	56	10	<20	157	0.03	<10	19	<10	<1	30
18	X10269	7.0	0.34	<5	55	<5	1.02	3	11	161	6947	5.07	<10	0.13	285	17	0.01	6	<10	32	<5	<20	132	0.02	<10	19	<10	<1	28
19	X10270	3.5	0.37	<5	45	<5	0.84	2	11	162	2858	4.77	<10	0.19	332	21	0.01	6	370	28	10	<20	64	0.02	<10	17	<10	<1	26
20	X10271	2.7	0.59	<5	60	<5	0.69	2	10	118	2197	4.86	<10	0.41	357	23	0.01	5	570	24	10	<20	58	0.02	<10	28	<10	<1	50
21	X10272	3.4	0.58	<5	65	<5	0.71	2	10	144	2885	4.50	<10	0.44	487	20	0.01	5	280	40	10	<20	55	0.02	<10	20	<10	1	46
22	X10273	2.6	0.73	<5	75	<5	0.57	2	9	149	2316	5.50	<10	0.56	401	18	0.01	6	500	24	15	<20	66	0.02	<10	47	<10	<1	53
23	X10274	4.0	0.39	<5	55	<5	1.12	4	13	176	3905	5.65	<10	0.24	606	79	0.01	8	160	54	10	<20	119	0.03	<10	27	<10	<1	40
24	X10275	4.1	0.48	<5	55	<5	1.60	3	12	127	4818	5.47	<10	0.30	456	24	0.01	6	270	32	10	<20	202	0.02	<10	33	<10	<1	34
25	X10276	3.7	0.42	<5	55	<5	1.52	3	21	141	3963	6.02	<10	0.24	399	56	0.01	8	290	26	5	<20	198	0.02	<10	24	<10	<1	34

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10277	3.8	0.39	<5	65	<5	1.69	3	28	143	3949	6.65	<10	0.22	386	57	0.01	7	260	28	10	<20	223	0.02	<10	22	<10	<1	27
27	X10278	3.2	0.71	<5	70	<5	1.26	2	10	159	3216	5.07	<10	0.61	600	23	0.01	7	480	26	15	<20	151	0.03	<10	50	<10	<1	44
28	X10279	2.2	0.77	<5	65	<5	1.75	2	8	164	1989	5.08	<10	0.69	729	16	0.01	7	640	36	15	<20	216	0.03	<10	54	<10	<1	49
29	X10280	2.3	0.83	<5	70	<5	1.84	4	8	146	1843	5.33	<10	0.77	822	21	0.01	9	730	36	35	<20	166	0.02	<10	60	<10	1	55
30	X10281	3.9	0.80	<5	55	<5	1.95	4	9	126	4435	5.76	<10	0.76	939	14	0.01	8	650	40	30	<20	170	0.03	<10	59	<10	1	63
31	X10282	<0.2	1.14	<5	245	20	0.65	<1	8	90	12	2.26	<10	0.74	620	1	0.14	8	960	20	10	<20	127	0.12	<10	56	<10	4	50
32	X10283	3.2	1.25	20	70	<5	1.00	3	22	63	2743	3.60	20	0.70	200	216	0.04	10	400	80	15	<20	68	0.04	<10	49	<10	7	275
33	X10284	2.9	0.92	10	50	<5	1.72	3	10	122	2837	5.19	<10	0.89	817	18	0.01	7	620	74	25	<20	163	0.02	<10	49	<10	<1	71
34	X10285	3.8	0.79	15	55	<5	1.57	2	11	118	2315	4.60	<10	0.74	884	29	0.01	6	600	38	15	<20	84	0.02	<10	25	<10	1	50
35	X10286	3.2	0.82	<5	50	<5	2.36	1	9	88	1709	3.91	<10	0.67	1068	10	0.01	3	470	24	10	<20	155	0.03	<10	23	<10	3	39
QC DATA:																													
Repeat:																													
1	X10252	6.2	0.22	5	55	<5	0.56	10	15	135	3284	7.50	<10	<0.01	306	85	<0.01	7	360	88	15	<20	40	0.02	<10	13	<10	<1	425
10	X10261	2.7	0.52	20	50	<5	0.71	8	10	154	1565	5.98	<10	0.19	400	38	0.01	9	640	36	20	<20	49	0.02	<10	18	<10	<1	223
19	X10270	3.7	0.41	<5	50	<5	0.85	2	11	169	2931	4.87	<10	0.19	338	20	0.01	7	370	26	10	<20	63	0.02	<10	20	<10	<1	26
Resplit:																													
1	X10252	6.4	0.20	<5	55	<5	0.60	11	14	158	3188	7.18	<10	0.01	300	94	<0.01	9	360	96	20	<20	40	0.02	<10	14	<10	<1	457
Standard:																													
PB113A		11.5	0.29	45	90	<5	1.65	42	3	7	2314	1.05	<10	0.11	1517	71	0.02	2	30	5490	20	<20	100	0.02	<10	7	<10	<1	6963

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish



ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5674S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5691

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

5-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07187
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	X10357	0.54	0.016		
2	X10358	0.33	0.010		
3	X10359	0.47	0.014		
4	X10360	0.31	0.009		
5	X10361	0.37	0.011		
6	X10362	0.71	0.021		
7	X10363	0.54	0.016		
8	X10364	0.51	0.015		
9	X10365	0.36	0.010		
10	X10366	0.28	0.008		
11	X10367	0.51	0.015		
12	X10368	0.36	0.010		
13	X10369	0.54	0.016		
14	X10370	0.35	0.010		
15	X10371	0.39	0.011		
16	X10372	0.83	0.024		
17	X10373	0.49	0.014		
18	X10374	0.34	0.010		
19	X10375	0.09	0.003		
20	X10376	0.54	0.016		
21	X10377	0.27	0.008		
22	X10378	0.29	0.008		
23	X10379	0.50	0.015		
24	X10380	0.56	0.016	44.7	1.30
25	X10381	0.60	0.017	191	5.57
26	X10382	<0.03	<0.001		
27	X10383	0.08	0.002		
28	X10384	0.36	0.010		
29	X10385	0.55	0.016		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5691 5-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
30	X10386	0.31	0.009		
31	X10387	0.43	0.013		
32	X10388	0.82	0.024		
33	X10389	0.48	0.014		
34	X10390	0.53	0.015		
35	X10391	0.68	0.020		
QC DATA:					
Repeat:					
1	X10357	0.55	0.016		
10	X10366	0.30	0.009		
11	X10367	0.48	0.014		
13	X10369	0.50	0.015		
15	X10371	0.40	0.012		
16	X10372	0.87	0.025		
17	X10373	0.48	0.014		
19	X10375	0.06	0.002		
24	X10380			45.7	1.33
25	X10381			185	5.40
Resplits:					
1	X10357	0.50	0.015		
Standard:					
SN26		8.58	0.250		
PB113				23.2	0.68

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5691

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07187
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10357	1.9	0.79	<5	45	<5	0.91	2	13	170	1679	5.28	<10	0.57	622	14	0.01	7	620	28	<5	<20	77	0.02	<10	48	<10	1	54
2	X10358	1.4	0.94	<5	40	<5	1.28	2	11	96	1130	4.61	<10	0.84	756	12	0.02	5	860	52	10	<20	107	0.02	<10	33	<10	1	73
3	X10359	2.1	0.95	<5	40	<5	1.55	3	10	120	1570	4.37	<10	0.83	839	11	0.02	5	790	50	<5	<20	146	0.02	<10	34	<10	2	84
4	X10360	2.3	0.94	<5	35	<5	1.24	2	10	87	1069	4.62	<10	0.80	791	11	0.02	5	870	44	15	<20	98	0.02	<10	32	<10	<1	79
5	X10361	2.1	1.05	<5	45	<5	1.16	2	11	112	1536	4.45	<10	0.97	889	11	0.01	4	780	58	10	<20	113	0.02	<10	35	<10	3	115
6	X10362	2.0	1.02	<5	50	<5	1.67	22	11	121	1097	4.61	<10	0.80	983	15	0.02	5	880	70	10	<20	188	0.02	<10	40	<10	2	609
7	X10363	2.9	0.94	10	50	<5	0.76	2	11	119	1415	4.62	<10	0.85	806	11	0.01	5	730	36	10	<20	74	0.02	<10	33	<10	1	111
8	X10364	5.9	0.73	<5	35	<5	0.64	5	11	97	1904	5.16	<10	0.62	678	17	0.01	9	820	72	25	<20	67	0.01	<10	26	<10	1	139
9	X10365	2.5	0.82	<5	45	<5	1.13	1	11	112	1173	4.13	<10	0.63	842	12	0.02	6	870	38	10	<20	123	0.02	<10	22	<10	2	85
10	X10366	2.2	0.78	<5	45	<5	1.29	1	10	122	1308	3.68	<10	0.56	778	13	0.02	5	820	28	5	<20	152	0.02	<10	24	<10	2	58
11	X10367	2.8	0.92	<5	40	<5	0.91	2	11	119	1541	4.31	<10	0.78	798	11	0.01	6	840	26	15	<20	83	0.02	<10	28	<10	2	58
12	X10368	4.2	0.47	25	35	<5	0.80	2	10	124	1827	4.26	<10	0.46	771	9	0.01	5	720	42	10	<20	68	0.02	<10	16	<10	1	26
13	X10369	4.8	0.39	85	40	<5	0.62	2	11	85	1535	4.82	<10	0.32	541	12	0.02	5	900	24	5	<20	47	0.02	<10	11	<10	<1	37
14	X10370	3.4	0.66	<5	50	<5	0.60	1	12	164	2607	4.42	<10	0.65	672	14	0.02	6	460	26	10	<20	66	0.02	<10	27	<10	2	44
15	X10371	2.2	1.02	5	40	<5	0.76	2	9	170	1338	4.77	<10	0.94	819	11	0.01	8	740	28	10	<20	69	0.02	<10	33	<10	1	55
16	X10372	3.2	0.80	<5	40	<5	0.77	2	14	115	2497	5.42	<10	0.75	698	10	0.01	6	580	34	10	<20	79	0.02	<10	34	<10	<1	41
17	X10373	2.6	1.11	60	45	<5	0.88	2	12	90	1143	5.09	<10	1.16	863	14	0.02	6	960	34	15	<20	77	0.03	<10	27	<10	3	63
18	X10374	2.9	1.13	25	45	<5	1.12	2	11	95	819	4.36	<10	1.33	1127	11	0.02	7	1010	38	20	<20	91	0.03	<10	25	<10	3	61
19	X10375	1.8	4.03	<5	65	45	0.40	4	44	36	53	9.40	<10	4.18	972	14	0.01	8	1130	90	45	<20	55	0.04	<10	104	<10	<1	147
20	X10376	3.1	1.04	160	40	<5	0.98	3	13	112	735	5.57	<10	1.21	1074	11	0.01	6	870	36	15	<20	80	0.03	<10	30	<10	2	48
21	X10377	1.9	1.19	50	40	<5	0.89	1	10	96	697	4.38	<10	1.31	1022	10	0.02	6	1010	38	15	<20	83	0.03	<10	31	<10	3	57
22	X10378	2.6	1.04	<5	35	<5	0.70	2	12	105	793	4.68	<10	0.97	700	13	0.02	5	970	40	15	<20	61	0.03	<10	27	<10	2	65
23	X10379	10.9	0.51	40	60	<5	0.46	2	12	169	5168	4.55	<10	0.47	522	10	0.01	7	230	32	10	<20	45	0.02	<10	24	<10	<1	36
24	X10380	>30	0.64	45	25	<5	0.90	4	9	172	3055	4.39	<10	0.76	1054	7	0.01	7	460	118	35	<20	60	0.02	<10	23	<10	<1	89
25	X10381	>30	0.30	125	45	<5	1.20	25	15	151	3081	6.33	<10	0.06	594	10	0.02	10	590	390	220	<20	80	0.03	<10	11	<10	1	103

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	10382	<0.2	1.05	<5	260	5	0.60	<1	7	89	8	2.23	<10	0.62	539	3	0.10	5	930	26	10	<20	96	0.09	<10	47	<10	<1	44
27	X10383	2.4	1.41	<5	50	<5	1.20	<1	13	109	1394	4.80	<10	1.27	841	7	0.01	2	850	42	<5	<20	107	0.03	<10	55	<10	4	89
28	10384	2.4	1.05	<5	40	<5	1.42	1	17	124	1163	5.05	<10	1.09	1072	8	0.01	5	860	28	10	<20	125	0.03	<10	46	<10	3	57
29	X10385	1.7	1.14	<5	40	<5	0.84	3	10	155	548	4.98	<10	1.12	904	11	0.01	9	750	30	20	<20	69	0.03	<10	44	<10	3	85
30	X10386	3.2	1.17	30	40	<5	1.01	3	21	56	2712	3.62	10	0.68	202	198	0.04	8	470	76	15	<20	57	0.04	<10	48	<10	6	277
31	X10387	4.2	0.76	10	40	<5	0.82	1	8	151	1225	4.43	<10	0.70	881	8	0.01	6	700	28	<5	<20	78	0.03	<10	30	<10	2	65
32	X10388	5.4	0.37	<5	45	<5	0.89	2	17	99	951	7.53	<10	0.31	711	10	0.01	6	770	56	<5	<20	69	0.03	<10	18	<10	<1	20
33	X10389	3.2	0.87	<5	65	<5	1.82	4	15	142	1407	6.56	<10	0.94	1424	10	<0.01	8	600	38	5	<20	243	0.04	<10	38	<10	2	116
34	X10390	4.0	0.55	55	95	<5	3.15	2	5	135	1186	3.67	<10	2.08	2289	9	<0.01	5	460	30	25	<20	128	0.03	<10	32	<10	6	32
35	X10391	3.4	1.41	40	40	<5	0.97	2	11	119	1451	4.87	<10	1.46	1007	12	0.01	7	1060	36	15	<20	75	0.02	<10	55	<10	2	86
QC DATA:																													
Repeat:																													
1	X10357	1.9	0.79	<5	45	<5	0.90	2	13	169	1657	5.25	<10	0.57	622	14	0.01	8	610	28	5	<20	83	0.02	<10	48	<10	2	53
10	X10366	2.0	0.78	<5	40	<5	1.27	1	10	121	1292	3.63	<10	0.56	770	14	0.02	6	830	28	5	<20	147	0.01	<10	25	<10	1	57
19	X10375	1.8	4.01	<5	65	40	0.40	3	44	35	51	9.40	<10	4.15	971	14	0.01	7	1100	88	40	<20	57	0.04	<10	104	<10	<1	148
Resplit:																													
1	X10357	2.1	0.82	<5	45	<5	0.98	3	13	169	1731	5.40	<10	0.61	665	14	0.01	8	660	28	<5	<20	91	0.03	<10	49	<10	<1	56
Standard:																													
PB113A		11.4	0.27	60	50	<5	1.68	38	3	6	2292	1.05	<10	0.10	1435	73	0.02	2	100	5438	25	<20	109	0.01	<10	7	<10	<1	6979

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5680S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5692

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07189
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X12176	0.66	0.019
2	X12177	0.53	0.015
3	X12178	0.85	0.025
4	X12179	0.58	0.017
5	X12180	0.64	0.019
6	X12181	1.28	0.037
7	X12182	0.46	0.013
8	X12183	0.50	0.015
9	X12184	0.72	0.021
10	X12185	0.66	0.019
11	X12186	0.76	0.022
12	X12187	0.85	0.025
13	X12188	0.62	0.018
14	X12189	0.80	0.023
15	X12190	0.83	0.024
16	X12191	0.57	0.017
17	X12192	0.65	0.019
18	X12193	0.61	0.018
19	X12194	0.71	0.021
20	X12195	0.85	0.025
21	X12196	0.49	0.014
22	X12197	1.12	0.033
23	X12198	0.91	0.027
24	X12199	0.58	0.017
25	X12200	1.60	0.047
26	X12201	0.47	0.014
27	X12202	0.74	0.022
28	X12203	0.65	0.019
29	X12204	0.44	0.013

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5692 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X12205	0.52	0.015
31	X12206	0.46	0.013
32	X12207	0.71	0.021
33	X12208	0.61	0.018
34	X12209	0.28	0.008
35	X12210	<0.03	<0.001

QC DATA:

Repeat:

1	X12176	0.68	0.020
10	X12185	0.73	0.021
19	X12194	0.68	0.020
23	X12198	0.81	0.024

Standard:

OXK48		3.49	0.102

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

29-Nov-07

ECO TECH ABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5692

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07189
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X12176	2.3	0.93	<5	65	<5	1.21	2	13	104	1476	6.24	<10	0.69	822	18	0.02	5	810	52	<5	<20	88	0.03	<10	86	<10	<1	88
2	X12177	2.3	0.73	<5	60	<5	1.41	2	14	126	1724	5.57	<10	0.48	959	13	0.01	6	510	32	<5	<20	107	0.03	<10	85	<10	1	111
3	X12178	3.5	0.95	<5	65	<5	0.84	2	11	128	2202	5.86	<10	0.68	779	16	0.01	6	570	54	5	<20	54	0.02	<10	108	<10	<1	89
4	X12179	1.5	1.00	<5	85	<5	1.40	1	12	153	1287	6.21	<10	0.77	751	17	0.02	6	890	30	<5	<20	96	0.03	<10	106	<10	1	65
5	X12180	1.9	0.94	<5	70	<5	1.46	2	17	103	1398	5.67	<10	0.74	740	20	0.02	5	980	70	<5	<20	94	0.04	<10	88	<10	3	100
6	X12181	2.5	0.97	60	55	<5	1.46	2	13	136	1132	5.54	<10	0.62	776	16	0.01	5	760	30	5	<20	67	0.03	<10	61	<10	1	55
7	X12182	1.3	0.97	<5	85	<5	1.89	2	14	121	1150	6.20	<10	0.67	863	19	0.02	7	940	26	<5	<20	143	0.02	<10	88	<10	1	52
8	X12183	1.5	1.18	<5	80	<5	1.04	3	19	168	1090	6.33	<10	0.86	687	21	0.02	10	990	38	25	<20	106	0.02	<10	93	<10	1	67
9	X12184	2.4	1.38	<5	65	<5	1.07	1	13	107	1972	5.85	<10	0.98	854	18	0.01	5	800	42	<5	<20	76	0.03	<10	79	<10	2	88
10	X12185	1.3	1.08	<5	60	<5	0.74	1	13	148	1208	5.21	<10	0.70	648	14	0.01	5	750	32	<5	<20	65	0.02	<10	66	<10	1	61
11	X12186	2.5	0.92	<5	65	<5	0.46	3	32	118	2158	8.11	<10	0.63	485	15	0.01	6	600	34	<5	<20	73	0.02	<10	90	<10	<1	57
12	X12187	3.1	0.77	<5	55	<5	0.48	2	14	155	2351	6.09	<10	0.52	550	14	0.01	7	450	30	<5	<20	58	0.02	<10	105	<10	<1	66
13	X12188	1.6	0.80	<5	55	<5	0.48	4	13	144	1295	6.20	<10	0.52	628	17	0.01	6	570	40	<5	<20	53	0.02	<10	117	<10	<1	125
14	X12189	3.4	0.91	<5	50	<5	0.68	2	12	159	2690	6.16	<10	0.65	817	14	0.01	6	640	32	<5	<20	71	0.02	<10	107	<10	<1	72
15	X12190	1.5	0.73	<5	65	<5	1.13	2	13	156	1416	5.33	<10	0.51	712	15	0.02	7	670	34	<5	<20	170	0.02	<10	96	<10	1	56
16	X12191	1.3	0.62	<5	70	<5	1.12	1	12	167	1090	5.54	<10	0.42	662	12	0.01	6	470	20	<5	<20	323	0.03	<10	107	<10	<1	46
17	X12192	2.0	1.02	<5	55	<5	1.26	2	14	131	1829	5.57	<10	0.71	808	21	0.01	5	660	42	<5	<20	95	0.03	<10	78	<10	1	104
18	X12193	1.9	1.14	<5	55	<5	1.02	2	13	165	1429	6.71	<10	0.79	1045	16	0.01	7	630	50	<5	<20	89	0.03	<10	111	<10	<1	102
19	X12194	1.6	1.10	10	60	<5	0.43	<1	14	168	1477	5.32	<10	0.59	538	12	<0.01	5	610	38	<5	<20	44	0.03	<10	78	<10	<1	72
20	X12195	2.5	0.77	<5	65	<5	0.81	1	14	169	1787	6.07	<10	0.51	626	13	0.01	8	510	40	<5	<20	141	0.02	<10	112	<10	<1	56
21	X12196	1.4	0.92	<5	95	<5	0.86	1	12	148	989	6.30	<10	0.61	828	16	0.01	5	690	28	<5	<20	91	0.03	<10	117	<10	<1	69
22	X12197	3.2	0.87	<5	60	<5	0.59	3	13	160	2942	5.98	<10	0.57	715	14	0.01	7	360	48	<5	<20	69	0.02	<10	104	<10	<1	91
23	X12198	3.4	0.97	10	65	<5	0.97	1	13	173	1649	5.83	<10	0.65	919	14	0.01	6	640	46	<5	<20	85	0.03	<10	93	<10	<1	89
24	X12199	1.6	0.85	<5	105	<5	1.07	1	12	183	1373	5.41	<10	0.60	911	15	0.01	6	560	30	<5	<20	80	0.03	<10	100	<10	<1	73
25	X12200	0.2	0.93	2040	90	45	0.95	2	32	28	60	4.95	10	2.10	734	7	0.19	110	1110	20	20	<20	53	0.09	<10	26	<10	9	60

ECO TECH LABORATORY LTD. | ICP CERTIFICATE OF ANALYSIS AS 2007-5692 | Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X12201	1.0	0.98	<5	125	<5	1.35	1	9	153	750	4.93	<10	0.73	1076	14	0.01	6	770	34	<5	<20	82	0.02	<10	86	<10	<1	79
27	X12202	1.8	0.93	<5	75	<5	0.81	2	13	186	1802	5.25	<10	0.70	742	13	0.01	7	650	40	<5	<20	73	0.02	<10	102	<10	<1	76
28	X12203	1.7	0.80	<5	55	<5	0.82	2	14	162	1539	5.23	<10	0.54	716	17	0.01	6	510	38	<5	<20	67	0.02	<10	86	<10	<1	59
29	X12204	1.1	0.91	<5	80	<5	1.22	2	11	159	737	4.94	<10	0.63	925	20	0.01	8	630	30	15	<20	110	0.02	<10	96	<10	<1	65
30	X12205	1.4	1.77	15	50	<5	2.79	2	10	186	747	5.03	<10	1.94	1998	15	<0.01	6	630	42	15	<20	155	0.03	<10	85	<10	3	100
31	X12206	1.3	1.26	15	50	<5	1.56	2	12	142	770	5.85	<10	0.96	1073	16	<0.01	6	710	34	10	<20	131	0.03	<10	75	<10	<1	79
32	X12207	2.7	1.29	5	50	<5	1.17	2	11	132	1653	5.63	<10	0.85	800	17	<0.01	6	610	42	5	<20	77	0.02	<10	83	<10	1	97
33	X12208	2.5	1.14	10	55	<5	1.26	2	12	156	1489	5.54	<10	0.74	779	12	0.01	6	500	48	<5	<20	98	0.03	<10	68	<10	1	64
34	X12209	3.0	1.50	20	55	<5	1.05	3	22	65	2601	3.87	20	0.70	210	213	0.05	9	490	76	10	<20	62	0.06	<10	53	<10	7	301
35	X12210	<0.2	1.02	<5	275	40	0.68	<1	8	101	8	2.44	<10	0.66	589	3	0.12	6	950	28	<5	<20	97	0.13	<10	52	<10	4	46
QC DATA:																													
Repeat:																													
1	X12176	2.2	0.92	<5	60	<5	1.16	3	13	105	1433	6.13	<10	0.67	798	18	0.02	5	800	50	<5	<20	82	0.02	<10	87	<10	<1	86
10	X12185	1.2	1.10	<5	60	<5	0.73	2	13	151	1200	5.23	<10	0.71	645	17	0.01	9	760	30	5	<20	53	0.02	<10	68	<10	<1	61
19	X12194	1.7	1.10	<5	65	<5	0.41	2	13	158	1460	5.15	<10	0.60	526	13	<0.01	6	600	36	<5	<20	40	0.02	<10	77	<10	<1	70
Resplit:																													
1	X12176	2.2	0.93	<5	60	<5	1.06	3	12	99	1507	5.94	<10	0.69	760	16	0.01	6	770	38	<5	<20	71	0.03	<10	87	<10	<1	88
Standard:																													
PB113A		11.2	0.35	45	70	<5	1.84	40	3	6	2303	1.19	<10	0.12	1565	69	0.02	2	100	5630	20	<20	97	0.01	<10	9	<10	<1	6961

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5682S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5693

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

5-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07193
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X12316	0.40	0.012
2	X12317	0.69	0.020
3	X12318	0.27	0.008
4	X12319	0.39	0.011
5	X12320	0.38	0.011
6	X12321	0.30	0.009
7	X12322	0.26	0.008
8	X12323	0.32	0.009
9	X12324	0.18	0.005
10	X12325	0.36	0.010
11	X12326	0.20	0.006
12	X12327	0.49	0.014
13	X12328	0.64	0.019
14	X12329	0.28	0.008
15	X12330	0.17	0.005
16	X12331	0.19	0.006
17	X12332	0.18	0.005
18	X12333	0.37	0.011
19	X12334	0.31	0.009
20	X12335	0.23	0.007
21	X12336	0.21	0.006
22	X12337	0.21	0.006
23	X12338	0.43	0.013
24	X12339	0.37	0.011
25	X12340	0.18	0.005
26	X12341	0.38	0.011
27	X12342	0.22	0.006
28	X12343	0.25	0.007
29	X12344	0.49	0.014

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5693 5-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X12345	0.46	0.013
31	X12346	<0.03	<0.001
32	X12347	1.82	0.053
33	X12348	0.40	0.012
34	X12349	0.47	0.014
35	X12350	0.28	0.008

QC DATA:

Repeat:

1	X12316	0.36	0.010
10	X12325	0.40	0.012
13	X12328	0.59	0.017
19	X12334	0.36	0.010
23	X12338	0.49	0.014
26	X12341	0.35	0.010

Resplits:

1	X12316	0.41	0.012

Standard:

SN26		8.55	0.249

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

29-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5693

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07193
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X12316	1.6	1.24	<5	60	<5	1.25	1	13	115	1479	5.02	<10	0.75	515	9	0.02	5	900	32	5	<20	107	0.02	<10	78	<10	4	33
2	X12317	1.9	1.23	<5	55	<5	1.42	<1	12	69	1695	4.38	<10	0.69	537	10	0.02	4	1020	26	5	<20	100	0.02	<10	50	<10	4	34
3	X12318	1.3	1.28	<5	80	<5	1.74	<1	12	112	1200	4.55	<10	0.79	661	11	0.02	4	970	26	<5	<20	133	0.02	<10	79	<10	6	34
4	X12319	1.4	1.27	<5	65	<5	1.27	2	14	107	1668	5.18	<10	0.89	550	12	0.03	7	880	28	15	<20	134	0.02	<10	116	<10	4	38
5	X12320	1.2	1.29	<5	110	<5	1.34	1	11	122	1414	4.76	<10	0.86	670	10	0.02	5	960	26	<5	<20	125	0.02	<10	98	<10	4	39
6	X12321	1.4	1.42	<5	60	<5	3.69	2	12	99	1234	4.56	<10	0.93	1583	11	0.02	5	900	28	10	<20	246	0.03	<10	66	<10	6	45
7	X12322	1.0	1.40	<5	75	<5	1.72	<1	11	68	844	3.77	<10	0.90	781	10	0.02	3	1010	30	10	<20	127	0.02	<10	50	<10	5	45
8	X12323	1.2	1.26	<5	50	<5	1.39	1	12	153	921	4.68	<10	0.82	656	10	0.02	6	660	30	10	<20	124	0.02	<10	102	<10	3	40
9	X12324	0.9	1.09	<5	70	<5	1.45	1	11	105	672	4.61	<10	0.77	616	8	0.03	4	780	24	<5	<20	162	0.02	<10	135	<10	3	44
10	X12325	2.4	1.05	<5	70	<5	1.37	1	12	132	2175	4.21	<10	0.73	570	9	0.02	5	860	24	<5	<20	126	0.02	<10	110	<10	3	42
11	X12326	1.1	0.95	<5	45	<5	1.35	1	11	125	1049	4.07	<10	0.72	604	11	0.03	4	580	22	<5	<20	142	0.02	<10	110	<10	2	41
12	X12327	0.7	1.13	<5	70	<5	1.30	2	14	207	716	5.40	<10	0.85	658	11	0.05	8	600	26	10	<20	176	0.03	<10	190	<10	2	56
13	X12328	1.5	1.13	<5	50	<5	1.62	<1	12	143	995	4.39	<10	0.87	742	8	0.03	5	590	26	<5	<20	203	0.03	<10	128	<10	3	57
14	X12329	1.7	0.97	<5	45	<5	1.37	2	14	107	1156	6.45	<10	0.61	569	10	0.02	5	730	24	<5	<20	96	0.03	<10	63	<10	3	39
15	X12330	1.0	1.23	<5	60	<5	1.19	2	12	128	879	5.56	<10	0.95	601	13	0.03	8	760	30	15	<20	107	0.02	<10	177	<10	3	52
16	X12331	0.8	1.02	<5	215	<5	2.21	1	11	104	825	4.88	<10	0.68	863	10	0.04	4	820	22	<5	<20	191	0.03	<10	143	<10	4	55
17	X12332	1.7	1.09	<5	65	<5	1.81	2	11	110	1145	5.35	<10	0.67	802	12	0.02	4	750	26	5	<20	123	0.02	<10	96	<10	3	48
18	X12333	1.7	1.11	<5	75	<5	2.05	2	15	100	1609	5.66	<10	0.81	906	10	0.03	6	770	24	<5	<20	257	0.04	<10	167	<10	3	69
19	X12334	1.2	1.07	<5	180	<5	1.86	1	13	128	967	4.94	<10	0.84	763	12	0.06	4	1000	24	<5	<20	178	0.07	<10	206	<10	6	75
20	X12335	1.4	1.22	<5	140	<5	2.05	1	13	120	1462	5.73	<10	0.97	862	11	0.05	7	860	34	<5	<20	313	0.05	<10	236	<10	4	74
21	X12336	1.1	1.14	<5	400	<5	2.06	1	9	110	1328	4.66	<10	0.88	774	9	0.04	4	1080	24	<5	<20	245	0.06	<10	151	<10	6	63
22	X12337	1.2	1.06	<5	55	<5	2.15	2	13	92	839	5.95	<10	0.71	788	10	0.02	5	970	26	<5	<20	131	0.03	<10	96	<10	5	39
23	X12338	2.3	1.12	<5	55	<5	0.83	2	19	125	2123	6.78	<10	0.74	417	17	0.02	6	640	28	<5	<20	67	0.02	<10	87	<10	2	35
24	X12339	1.7	1.30	<5	60	<5	0.87	1	12	126	1178	6.00	<10	0.83	591	11	0.02	5	740	30	5	<20	69	0.02	<10	92	<10	3	47
25	X12340	1.5	1.16	<5	45	<5	0.93	2	13	138	814	4.91	<10	0.78	542	9	0.02	5	910	28	5	<20	85	0.02	<10	72	<10	3	49

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X12341	2.1	1.22	<5	45	<5	1.73	2	13	156	1525	4.87	<10	0.90	845	12	0.02	8	690	28	20	<20	130	0.01	<10	82	<10	2	54
27	X12342	1.1	1.41	<5	105	<5	1.07	1	11	105	787	4.68	<10	1.00	601	11	0.02	5	1130	34	10	<20	94	0.02	<10	70	<10	3	58
28	X12343	1.2	1.30	<5	65	<5	1.15	2	12	103	1085	5.76	<10	0.94	605	13	0.03	5	850	32	10	<20	125	0.02	<10	137	<10	2	52
29	X12344	1.7	1.22	<5	80	<5	1.64	1	17	113	1766	6.00	<10	0.96	716	14	0.03	5	790	26	10	<20	143	0.02	<10	185	<10	2	56
30	X12345	2.3	1.35	10	50	<5	2.20	3	14	127	1771	5.33	<10	1.05	1010	13	0.02	8	790	30	15	<20	156	0.02	<10	103	<10	4	47
31	X12346	<0.2	0.03	15	<5	15	>10	<1	2	5	2	0.03	<10	2.14	24	<1	<0.01	<1	60	10	15	<20	6701	0.02	<10	3	<10	<1	<1
32	X12347	3.9	1.37	25	50	<5	1.11	3	23	64	8575	4.22	20	0.67	210	645	0.05	61	140	74	25	<20	62	0.03	<10	48	<10	6	75
33	X12348	1.9	1.15	<5	90	<5	1.34	1	11	113	1729	4.65	<10	0.88	671	10	0.02	4	650	30	<5	<20	127	0.02	<10	123	<10	3	53
34	X12349	2.0	1.39	<5	75	<5	1.91	1	15	108	1516	5.74	<10	1.08	840	11	0.02	6	940	32	10	<20	204	0.02	<10	192	<10	3	65
35	X12350	1.4	1.53	<5	70	<5	1.92	2	16	82	963	5.22	<10	1.13	894	13	0.02	5	1200	36	5	<20	139	0.02	<10	113	<10	3	68
QC DATA:																													
Repeat:																													
1	X12316	1.5	1.21	<5	60	<5	1.25	2	12	112	1488	5.02	<10	0.74	515	9	0.02	5	890	30	<5	<20	106	0.02	<10	76	<10	4	32
10	X12325	2.4	1.02	<5	80	<5	1.36	1	12	126	2152	4.14	<10	0.73	563	9	0.02	5	840	22	5	<20	127	0.02	<10	106	<10	3	42
19	X12334	1.4	1.01	<5	165	<5	1.80	2	12	118	923	4.69	<10	0.80	734	12	0.05	4	1000	26	5	<20	172	0.06	<10	191	<10	5	73
Resplit:																													
1	X12316	1.6	1.22	<5	65	<5	1.23	2	13	120	1546	4.87	<10	0.74	512	9	0.02	7	910	32	15	<20	93	0.02	<10	77	<10	3	34
Standard:																													
PB113A		11.8	0.30	50	65	<5	1.60	41	3	6	2271	1.19	<10	0.12	1550	64	0.02	3	100	5658	15	<20	97	<0.01	<10	10	<10	<1	6928

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
dl/5682S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5694

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

5-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07188
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10392	0.70	0.020
2	X10393	0.71	0.021
3	X10394	0.05	0.001
4	X10395	<0.03	<0.001
5	X10396	0.54	0.016
6	X10397	0.26	0.008
7	X10398	0.04	0.001
8	X10399	0.06	0.002
9	X10400	0.29	0.008
10	X10401	0.50	0.015
11	X10402	0.52	0.015
12	X10403	0.65	0.019
13	X10404	0.88	0.026
14	X10405	0.41	0.012
15	X10406	0.17	0.005
16	X10407	0.74	0.022
17	X10408	0.45	0.013
18	X10409	0.55	0.016
19	X10410	0.62	0.018
20	X10411	0.49	0.014
21	X10412	0.65	0.019
22	X10413	0.45	0.013
23	X10414	0.34	0.010
24	X10415	0.33	0.010
25	X10416	0.52	0.015
26	X10417	0.82	0.024
27	X10418	0.75	0.022
28	X10419	<0.03	<0.001
29	X10420	0.40	0.012

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5694 5-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X10421	0.39	0.011
31	X10422	0.29	0.008
32	X10423	1.84	0.054
33	X10424	0.32	0.009
34	X10425	0.39	0.011
35	X10426	0.45	0.013
QC DATA:			
Repeat:			
1	X10392	0.70	0.020
10	X10401	0.50	0.015
19	X10410	0.55	0.016
Resplits:			
1	X10392	0.65	0.019
Standard:			
SN26		8.57	0.250

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5694

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1


No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07188
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10392	6.7	0.64	10	50	<5	0.41	2	16	90	2087	6.70	<10	0.42	313	13	0.01	6	720	42	10	<20	49	0.03	<10	32	<10	<1	32
2	X10393	11.1	0.50	65	55	<5	0.80	2	18	140	3553	7.61	<10	0.36	465	11	0.01	8	720	46	<5	<20	64	0.02	<10	31	<10	<1	36
3	X10394	0.2	3.56	30	215	20	1.79	3	33	34	26	7.16	<10	3.56	1537	10	0.01	7	1100	70	40	<20	143	0.04	<10	105	<10	6	148
4	X10395	0.2	3.05	40	230	<5	4.02	4	29	32	38	6.26	<10	2.79	2031	14	0.01	10	1140	60	65	<20	391	0.03	<10	90	<10	7	137
5	X10396	2.8	0.96	30	60	<5	2.08	2	10	101	664	3.37	<10	1.22	1595	9	0.01	5	700	30	20	<20	195	0.03	<10	33	<10	3	55
6	X10397	2.1	1.72	85	65	<5	4.05	1	21	89	584	5.35	<10	1.55	2290	7	0.01	4	1010	44	15	<20	468	0.04	<10	51	<10	5	81
7	X10398	0.6	4.84	75	190	20	3.80	3	36	25	133	>10	<10	5.02	3562	12	0.01	5	1180	90	45	<20	273	0.07	<10	156	<10	10	230
8	X10399	0.9	3.36	60	155	<5	1.69	3	25	29	287	7.25	<10	3.53	1940	10	0.01	6	1210	66	45	<20	102	0.04	<10	88	<10	9	180
9	X10400	2.8	1.14	30	55	<5	1.37	2	13	245	709	4.72	<10	1.35	1433	11	0.01	9	670	32	20	<20	116	0.03	<10	50	<10	3	70
10	X10401	4.1	0.94	60	50	<5	0.86	2	13	118	2047	4.66	<10	1.01	854	9	0.01	7	550	28	15	<20	92	0.02	<10	42	<10	2	61
11	X10402	2.7	1.41	<5	65	<5	1.29	2	13	115	1383	5.75	<10	1.51	1325	13	0.01	7	830	38	20	<20	124	0.03	<10	70	<10	2	79
12	X10403	2.8	1.47	30	60	<5	1.70	2	12	158	1627	5.91	<10	1.74	1444	13	0.01	8	810	38	25	<20	156	0.03	<10	74	<10	3	65
13	X10404	8.1	0.53	35	55	<5	2.01	4	17	202	2079	6.56	<10	0.98	1431	11	0.01	10	650	130	20	<20	167	0.03	<10	45	<10	2	85
14	X10405	3.8	1.24	30	60	<5	1.76	3	12	145	1505	5.71	<10	1.70	1495	12	0.01	8	920	38	35	<20	119	0.03	<10	68	<10	2	72
15	X10406	1.9	1.53	15	80	<5	0.63	3	11	133	589	4.90	<10	1.33	770	14	0.01	8	1120	44	30	<20	69	0.02	<10	78	<10	2	95
16	X10407	3.4	1.46	5	60	<5	1.76	3	14	120	2091	5.84	<10	1.50	1427	12	0.01	6	740	36	20	<20	150	0.03	<10	94	<10	<1	83
17	X10408	2.6	1.54	20	70	<5	1.81	2	11	129	1530	5.15	<10	1.73	1349	12	0.01	6	820	36	25	<20	200	0.03	<10	89	<10	2	66
18	X10409	3.5	1.44	<5	65	<5	1.48	2	13	127	2266	5.73	<10	1.46	1118	11	0.01	6	770	32	20	<20	170	0.03	<10	120	<10	<1	58
19	X10410	3.6	1.18	<5	55	<5	1.75	2	17	124	2003	7.73	<10	1.43	1256	12	0.01	7	1260	34	20	<20	168	0.04	<10	111	<10	<1	54
20	X10411	2.5	1.23	25	40	<5	2.59	2	12	110	1332	5.26	<10	1.85	1736	11	0.01	5	830	30	25	<20	239	0.03	<10	61	<10	2	58
21	X10412	3.9	1.10	10	55	<5	2.90	2	13	155	2386	5.71	<10	1.75	1933	10	0.01	7	610	32	20	<20	287	0.04	<10	56	<10	3	50
22	X10413	4.4	0.85	15	45	<5	2.67	3	12	110	1781	5.93	<10	1.55	1957	11	0.01	6	770	32	25	<20	224	0.04	<10	44	<10	3	46
23	X10414	4.2	0.45	35	55	<5	3.54	<1	12	122	1319	4.92	<10	1.73	3274	11	0.01	4	950	40	20	<20	300	0.06	<10	25	<10	9	21
24	X10415	4.6	0.47	30	65	<5	2.28	1	13	116	1681	5.60	<10	1.15	2398	11	0.01	7	1040	38	15	<20	249	0.05	<10	40	<10	7	22
25	X10416	3.9	0.97	35	55	<5	1.55	1	18	128	2598	5.78	<10	1.10	1224	11	0.01	8	1020	40	10	<20	153	0.04	<10	76	<10	5	45

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10417	2.5	1.50	110	70	<5	1.63	3	13	96	2061	5.16	<10	1.55	1160	13	0.01	6	1990	50	20	<20	155	0.04	<10	77	<10	9	58
27	X10418	2.6	1.44	25	55	<5	1.45	1	13	140	2454	5.11	<10	1.61	1220	11	0.01	7	820	36	15	<20	140	0.03	<10	73	<10	3	56
28	X10419	<0.2	1.20	<5	315	20	0.67	<1	7	138	8	2.35	<10	0.69	583	<1	0.13	6	900	30	<5	<20	120	0.11	<10	52	<10	2	48
29	X10420	2.4	1.25	<5	65	<5	1.67	2	11	97	1908	4.65	<10	1.54	1244	11	0.01	6	830	32	25	<20	173	0.03	<10	63	<10	5	52
30	X10421	2.5	1.03	<5	50	<5	1.61	2	13	110	1914	5.21	<10	1.40	1283	11	0.01	5	900	32	15	<20	137	0.03	<10	54	<10	3	49
31	X10422	2.7	1.39	<5	65	<5	1.56	2	13	69	1652	5.54	<10	1.66	1013	13	0.02	5	1270	38	20	<20	136	0.04	<10	62	<10	5	68
32	X10423	3.9	1.22	30	85	<5	1.08	3	24	66	8736	4.42	10	0.69	217	640	0.05	72	40	88	35	<20	111	0.05	<10	46	<10	9	79
33	X10424	2.0	1.58	<5	70	<5	1.74	2	13	105	1503	4.98	<10	1.72	997	14	0.02	7	1090	42	30	<20	190	0.03	<10	60	<10	4	64
34	X10425	2.4	1.51	<5	50	<5	1.74	2	13	76	1944	5.21	<10	1.68	998	12	0.02	7	1110	38	25	<20	187	0.03	<10	92	<10	4	52
35	X10426	2.4	1.43	<5	60	<5	2.14	2	16	105	1887	5.74	<10	1.32	892	11	0.01	6	1000	36	25	<20	252	0.03	<10	86	<10	3	45
QC DATA:																													
Repeat:																													
1	X10392	6.7	0.71	20	60	<5	0.43	2	16	94	2153	6.89	<10	0.45	324	14	0.01	6	730	42	15	<20	52	0.03	<10	36	<10	<1	32
10	X10401	4.2	1.00	65	55	<5	0.88	1	14	126	2109	4.77	<10	1.04	878	8	0.01	5	540	28	10	<20	98	0.03	<10	45	<10	2	63
19	X10410	3.4	1.16	<5	50	<5	1.65	3	16	124	1967	7.31	<10	1.35	1182	14	0.01	10	1220	36	30	<20	171	0.04	<10	110	<10	<1	51
Resplit:																													
1	X10392	6.6	0.66	10	50	<5	0.45	2	15	96	2109	6.31	<10	0.50	318	13	0.01	8	720	42	15	<20	57	0.03	<10	36	<10	<1	36
Standard:																													
PB113A		11.8	0.30	65	70	<5	1.75	44	2	7	2289	1.11	<10	0.13	1493	71	0.02	4	70	5550	20	<20	96	<0.01	<10	10	<10	<1	6990

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish



ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5674S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5695

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07186
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10322	0.56	0.016
2	X10323	0.11	0.003
3	X10324	0.29	0.008
4	X10325	0.29	0.008
5	X10326	0.67	0.020
6	X10327	0.64	0.019
7	X10328	0.40	0.012
8	X10329	0.34	0.010
9	X10330	0.44	0.013
10	X10331	0.26	0.008
11	X10332	0.63	0.018
12	X10333	0.47	0.014
13	X10334	0.23	0.007
14	X10335	0.48	0.014
15	X10336	0.76	0.022
16	X10337	0.49	0.014
17	X10338	0.98	0.029
18	X10339	0.88	0.026
19	X10340	1.01	0.029
20	X10341	0.37	0.011
21	X10342	0.44	0.013
22	X10343	0.33	0.010
23	X10344	0.36	0.010
24	X10345	0.66	0.019
25	X10346	0.40	0.012
26	X10347	0.78	0.023
27	X10348	1.07	0.031
28	X10349	0.57	0.017
29	X10350	0.55	0.016

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5795 4-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X10351	<0.03	<0.001
31	X10352	0.51	0.015
32	X10353	0.60	0.017
33	X10354	1.90	0.055
34	X10355	0.74	0.022
35	X10356	0.43	0.013

QC DATA:

Repeat:

1	X10322	0.51	0.015
10	X10331	0.27	0.008
19	X10340	1.07	0.031

Resplits:

1	X10322	0.58	0.017

Standard:

OXK48		3.55	0.104

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5695

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07186
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10322	1.6	0.53	10	45	<5	2.34	2	8	90	1525	4.53	<10	0.39	593	6	0.02	<1	620	16	<5	<20	210	<0.01	<10	38	<10	3	65
2	X10323	0.6	0.77	10	60	<5	2.62	1	6	51	414	3.19	<10	0.59	1029	6	0.03	2	1080	16	<5	<20	189	<0.01	<10	22	<10	5	68
3	X10324	0.9	0.80	10	80	<5	2.04	2	6	37	620	3.27	<10	0.62	852	8	0.02	1	1110	22	<5	<20	76	<0.01	<10	17	<10	4	97
4	X10325	2.8	0.95	15	40	<5	1.41	2	9	104	1342	4.91	<10	0.74	862	8	0.02	<1	790	10	<5	<20	66	<0.01	<10	28	<10	3	85
5	X10326	22.2	0.33	25	40	20	0.70	3	10	125	1194	8.42	<10	0.20	439	6	0.03	<1	800	32	5	<20	27	<0.01	<10	18	<10	1	24
6	X10327	2.7	0.67	30	35	<5	0.57	2	16	118	1077	5.93	<10	0.47	562	13	0.02	<1	740	12	<5	<20	21	<0.01	<10	30	<10	2	52
7	X10328	0.9	0.76	10	40	<5	0.62	2	10	123	722	5.18	<10	0.55	547	38	0.02	1	770	8	<5	<20	26	<0.01	<10	30	<10	3	47
8	X10329	1.6	0.69	25	35	<5	0.89	2	14	117	1162	5.48	<10	0.64	794	32	0.02	<1	780	22	<5	<20	37	<0.01	<10	29	<10	4	64
9	X10330	2.9	0.56	15	30	<5	0.69	2	10	142	2694	4.55	<10	0.48	658	6	0.02	2	520	24	<5	<20	31	<0.01	<10	28	<10	2	46
10	X10331	2.5	0.24	5	30	<5	0.62	2	17	163	1922	3.26	<10	0.19	439	8	0.02	3	230	30	<5	<20	37	<0.01	<10	13	<10	1	13
11	X10332	3.5	0.63	15	40	<5	0.98	2	18	136	2855	5.31	<10	0.40	725	41	0.02	<1	560	20	<5	<20	57	<0.01	<10	34	<10	2	44
12	X10333	3.4	0.69	25	35	<5	1.24	2	8	122	1216	5.69	<10	0.50	919	6	0.02	<1	850	16	<5	<20	63	<0.01	<10	25	<10	3	51
13	X10334	4.7	0.24	15	35	5	1.15	3	14	127	962	5.90	<10	0.15	739	14	0.03	<1	790	40	<5	<20	60	<0.01	<10	12	<10	2	32
14	X10335	3.2	0.60	20	40	<5	1.36	2	10	104	947	6.28	<10	0.65	1264	9	0.03	<1	710	20	5	<20	51	<0.01	<10	25	<10	3	59
15	X10336	3.0	0.73	15	35	<5	0.73	2	16	122	1603	5.69	<10	0.57	725	36	0.02	<1	700	16	<5	<20	38	<0.01	<10	27	<10	3	61
16	X10337	8.3	0.47	20	30	<5	0.78	2	12	126	1662	6.08	<10	0.46	574	8	0.02	<1	720	46	<5	<20	36	<0.01	<10	18	<10	2	43
17	X10338	11.3	0.33	25	40	<5	1.43	5	10	139	2599	7.22	<10	0.76	1082	6	0.03	<1	410	308	5	<20	55	<0.01	<10	18	<10	2	189
18	X10339	7.4	0.58	15	35	<5	0.58	2	15	118	3119	6.23	<10	0.49	474	9	0.02	<1	590	20	<5	<20	28	<0.01	<10	33	<10	2	45
19	X10340	11.1	0.79	35	35	<5	0.94	3	10	132	3131	4.88	<10	0.80	912	11	0.02	1	540	44	<5	<20	38	<0.01	<10	28	<10	3	112
20	X10341	2.0	0.81	20	50	<5	1.67	2	8	109	1078	5.21	<10	0.80	1053	7	0.02	<1	720	40	<5	<20	84	<0.01	<10	43	<10	4	93
21	X10342	1.9	0.71	10	35	<5	0.73	2	10	129	1156	4.95	<10	0.52	553	9	0.02	1	600	26	<5	<20	42	<0.01	<10	36	<10	2	74
22	X10343	4.8	0.42	10	35	<5	1.01	2	16	195	2788	3.84	<10	0.29	608	9	0.02	3	320	32	<5	<20	67	<0.01	<10	22	<10	2	45
23	X10344	5.0	0.28	5	35	<5	1.03	2	10	248	2820	2.86	<10	0.16	549	9	0.02	4	230	28	<5	<20	79	<0.01	<10	16	<10	2	26
24	X10345	1.9	0.60	10	50	<5	1.96	2	11	120	1283	5.10	<10	0.39	863	15	0.03	1	770	34	<5	<20	143	<0.01	<10	39	<10	3	63
25	X10346	1.0	0.74	10	55	<5	2.05	2	13	102	841	5.55	<10	0.62	867	11	0.03	<1	890	22	<5	<20	280	<0.01	<10	48	<10	4	97

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10347	3.4	0.66	10	45	<5	1.60	3	12	125	2947	5.00	<10	0.49	772	6	0.02	1	620	24	<5	<20	124	<0.01	<10	41	<10	3	79
27	X10348	5.4	0.90	15	35	<5	0.80	3	11	132	4371	4.56	<10	0.69	639	6	0.02	1	640	14	<5	<20	52	<0.01	<10	34	<10	3	65
28	X10349	5.1	0.97	15	40	<5	0.69	3	8	102	2176	5.86	<10	0.73	624	9	0.02	<1	870	16	<5	<20	48	<0.01	<10	35	<10	3	106
29	X10350	8.0	0.49	15	35	5	0.96	2	7	128	1843	5.00	<10	0.29	531	15	0.02	1	720	40	<5	<20	69	<0.01	<10	15	<10	3	37
30	X10351	<0.2	1.03	10	250	<5	0.62	<1	6	99	5	2.15	<10	0.57	531	<1	0.12	6	920	10	<5	<20	100	0.14	<10	39	<10	5	45
31	X10352	1.3	1.21	15	110	<5	1.02	2	6	152	873	4.99	<10	0.86	711	10	0.03	2	920	8	<5	<20	85	<0.01	<10	49	<10	4	85
32	X10353	3.2	0.71	10	45	<5	0.75	3	7	180	2926	4.25	<10	0.48	555	9	0.02	3	620	34	<5	<20	67	<0.01	<10	33	<10	3	107
33	X10354	4.0	1.06	35	40	<5	1.01	3	19	57	8579	4.05	20	0.58	201	589	0.05	65	610	52	20	<20	62	0.04	<10	36	<10	8	75
34	X10355	2.1	0.63	10	35	<5	0.65	3	13	89	1785	4.95	<10	0.48	474	9	0.02	<1	750	18	<5	<20	57	<0.01	<10	27	<10	4	71
35	X10356	1.2	0.79	10	40	<5	1.16	2	9	107	910	6.12	<10	0.63	619	7	0.03	<1	850	14	<5	<20	103	<0.01	<10	45	<10	4	55
QC DATA:																													
Repeat:																													
1	X10322	1.7	0.51	10	40	<5	2.36	2	8	89	1551	4.55	<10	0.39	604	6	0.03	<1	630	16	<5	<20	210	<0.01	<10	36	<10	3	67
10	X10331	2.3	0.24	5	30	<5	0.63	2	17	163	1951	3.28	<10	0.18	445	9	0.02	3	240	30	<5	<20	35	<0.01	<10	13	<10	1	14
19	X10340	10.8	0.75	35	35	<5	0.97	3	10	121	3067	4.80	<10	0.79	890	10	0.02	1	540	42	<5	<20	39	<0.01	<10	26	<10	3	108
Resplit:																													
1	X10322	1.5	0.58	10	40	<5	2.50	2	8	99	1471	4.61	<10	0.45	613	7	0.03	<1	700	16	<5	<20	216	<0.01	<10	42	<10	4	74
Standard:																													
Pb113A		11.6	0.28	45	70	<5	1.65	38	2	<1	2235	1.03	<10	0.10	1468	63	0.02	1	100	5434	5	<20	86	0.01	<10	8	<10	1	6982

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5694
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5696

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

29-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07199
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05728	1.17	0.034
2	X05729	<0.03	<0.001
3	X05730	0.76	0.022
4	X05731	0.35	0.010
5	X05732	0.28	0.008
6	X05733	0.36	0.010
7	X05734	0.35	0.010
8	X05735	0.37	0.011
9	X05736	0.25	0.007
10	X05737	0.30	0.009
11	X05738	0.26	0.008
12	X05739	0.24	0.007
13	X05740	0.16	0.005
14	X05741	0.30	0.009
15	X05742	0.95	0.028
16	X05743	1.35	0.039
17	X05744	0.41	0.012
18	X05745	0.48	0.014
19	X05746	0.29	0.008
20	X05747	0.42	0.012
21	X05748	0.32	0.009
22	X05749	0.42	0.012
23	X05750	0.18	0.005
24	X05751	0.42	0.012
25	X05752	0.44	0.013
26	X05753	0.33	0.010

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5696 29-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	X05754	0.44	0.013
28	X05755	0.34	0.010
29	X05756	0.29	0.008
30	X05757	0.31	0.009
31	X05758	0.50	0.015
32	X05759	0.51	0.015
33	X05760	0.58	0.017
34	X05761	0.59	0.017
35	X05762	0.61	0.018

QC DATA:

Repeat:

1	X05728	1.17	0.034
10	X05737	0.32	0.009
19	X05746	0.29	0.008

Resplits:

1	X05728	1.07	0.031

Standard:

OXK48		3.50	0.102

AU: 30g FA/AA-Finish

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

30-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 2007-5696

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07199
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05728	3.5	0.82	<5	90	<5	2.04	4	13	96	3433	4.16	<10	0.47	754	16	0.01	9	560	26	30	<20	146	<0.01	<10	40	<10	4	65
2	X05729	<0.2	0.03	10	<5	<5	>10	<1	1	3	6	0.03	<10	2.08	32	<1	<0.01	<1	70	8	<5	<20	7410	0.02	<10	4	<10	<1	<1
3	X05730	2.4	0.93	<5	190	<5	2.31	3	14	91	2522	5.96	<10	0.56	829	16	0.02	8	890	26	20	<20	192	0.04	<10	107	<10	6	72
4	X05731	1.2	0.94	<5	270	<5	1.89	2	10	87	969	4.00	<10	0.58	712	12	0.03	4	850	26	10	<20	160	0.04	<10	48	<10	7	64
5	X05732	1.1	0.94	15	90	<5	1.49	2	13	124	499	4.04	<10	0.54	759	12	0.01	7	760	28	15	<20	96	0.03	<10	23	<10	5	58
6	X05733	1.4	0.83	<5	155	<5	2.60	2	10	80	1220	3.30	<10	0.39	1022	12	0.01	4	810	24	10	<20	161	0.03	<10	27	<10	7	55
7	X05734	1.3	0.87	<5	265	<5	2.30	2	9	93	1075	3.75	<10	0.52	847	11	0.02	5	860	26	10	<20	176	0.05	<10	43	<10	6	62
8	X05735	1.1	0.86	<5	295	<5	2.44	2	8	76	1093	3.45	<10	0.53	859	11	0.02	4	820	28	5	<20	216	0.05	<10	39	<10	6	58
9	X05736	0.8	0.90	<5	235	<5	1.98	1	9	81	722	3.36	<10	0.55	805	12	0.02	3	900	28	5	<20	152	0.05	<10	32	<10	6	61
10	X05737	1.1	0.81	<5	170	<5	2.61	2	11	70	856	4.30	<10	0.47	927	13	0.02	6	810	28	15	<20	187	0.06	<10	52	<10	6	64
11	X05738	1.7	0.72	<5	125	<5	4.23	2	10	99	1112	2.71	<10	0.36	1298	14	0.01	5	790	32	15	<20	350	0.05	<10	16	<10	6	49
12	X05739	1.2	0.87	<5	200	<5	2.55	2	10	62	637	3.00	<10	0.48	911	18	0.02	4	1040	34	15	<20	182	0.06	<10	28	<10	5	78
13	X05740	0.7	0.73	<5	540	<5	3.35	2	6	70	543	2.44	<10	0.40	947	10	0.02	2	970	28	<5	<20	259	0.06	<10	24	<10	6	57
14	X05741	2.9	1.36	30	40	<5	1.04	4	22	59	2574	3.68	20	0.68	205	204	0.04	11	470	68	25	<20	59	0.04	<10	51	<10	7	275
15	X05742	2.7	0.81	5	110	<5	4.22	2	10	89	1910	2.56	<10	0.45	1316	10	0.01	3	670	32	5	<20	202	0.06	<10	17	<10	8	64
16	X05743	7.4	0.82	15	80	<5	3.03	4	24	104	6072	4.45	<10	0.42	997	15	0.01	8	400	52	20	<20	171	0.03	<10	24	<10	5	78
17	X05744	2.4	0.82	<5	190	<5	3.10	2	7	59	1200	2.18	<10	0.38	1038	29	0.01	3	940	32	10	<20	192	0.05	<10	19	<10	7	74
18	X05745	2.7	0.91	5	160	<5	3.61	<1	10	59	895	2.36	<10	0.43	1252	15	0.01	1	1020	42	5	<20	205	0.06	<10	18	<10	10	71
19	X05746	3.4	0.89	5	125	<5	3.16	1	10	50	834	2.57	<10	0.46	1200	15	0.01	4	1050	36	5	<20	149	0.06	<10	17	<10	7	81
20	X05747	3.0	1.05	10	125	<5	4.08	2	10	87	765	2.80	<10	0.51	1481	18	0.01	4	1040	38	20	<20	150	0.05	<10	19	<10	6	106
21	X05748	2.1	1.03	<5	160	<5	3.98	2	9	44	659	2.61	<10	0.50	1427	19	0.01	3	1080	58	15	<20	169	0.06	<10	19	<10	7	112
22	X05749	5.0	0.84	5	145	<5	3.55	4	9	88	1138	2.36	<10	0.45	1169	37	0.02	5	1040	84	20	<20	175	0.05	<10	18	<10	8	154
23	X05750	0.8	0.86	<5	340	<5	3.29	3	8	40	500	2.58	<10	0.47	1023	25	0.03	2	1130	36	10	<20	222	0.07	<10	30	<10	7	95
24	X05751	1.9	0.86	<5	195	<5	2.83	2	10	108	1264	3.02	<10	0.50	905	18	0.03	5	950	40	10	<20	167	0.06	<10	38	<10	7	108
25	X05752	3.6	0.75	<5	75	<5	2.89	3	14	81	2353	2.82	<10	0.45	888	26	0.02	4	780	30	10	<20	186	0.05	<10	24	<10	6	142

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05753	1.1	1.02	<5	225	<5	2.38	2	11	82	961	3.43	<10	0.67	783	17	0.04	5	1030	30	10	<20	284	0.09	<10	51	<10	6	73
27	X05754	3.4	0.71	<5	90	<5	2.55	3	12	95	3602	2.61	<10	0.48	687	26	0.04	3	540	32	10	<20	193	0.05	<10	28	<10	6	58
28	X05755	1.1	0.92	<5	180	<5	2.31	2	9	79	1099	2.98	<10	0.52	727	24	0.04	4	1150	58	5	<20	161	0.07	<10	39	<10	7	88
29	X05756	0.6	0.81	5	345	<5	2.80	1	8	74	893	2.70	<10	0.46	748	244	0.03	2	1020	30	<5	<20	185	0.07	<10	33	<10	6	62
30	X05757	0.8	1.00	<5	370	<5	2.39	2	9	115	1123	3.28	<10	0.65	794	25	0.05	5	960	34	15	<20	275	0.08	<10	46	<10	5	78
31	X05758	0.8	0.78	<5	335	<5	2.35	1	7	93	960	2.36	<10	0.45	680	25	0.03	4	840	24	10	<20	139	0.06	<10	28	<10	5	60
32	X05759	2.1	0.92	15	105	<5	2.84	2	9	123	2209	2.71	<10	0.56	910	48	0.02	5	720	30	15	<20	74	0.04	<10	21	<10	6	66
33	X05760	1.6	0.89	10	115	<5	4.01	3	10	67	1760	2.41	<10	0.48	981	18	0.02	5	940	30	25	<20	128	0.05	<10	18	<10	10	78
34	X05761	1.6	0.89	10	145	<5	2.23	1	9	94	1907	1.66	<10	0.49	680	218	0.02	3	1020	26	10	<20	48	0.05	<10	13	<10	7	48
35	X05762	1.7	0.89	<5	165	<5	2.98	<1	10	66	2024	2.11	<10	0.47	689	67	0.02	2	1010	28	<5	<20	86	0.06	<10	24	<10	7	40
QC DATA:																													
Repeat:																													
1	X05728	3.6	0.83	<5	95	<5	2.02	2	13	96	3387	4.10	<10	0.47	747	14	0.01	5	580	28	25	<20	142	0.02	<10	41	<10	5	65
10	X05737	1.0	0.83	<5	175	<5	2.63	2	11	71	853	4.35	<10	0.48	929	14	0.02	6	820	30	15	<20	186	0.06	<10	54	<10	5	64
19	X05746	3.4	0.95	5	130	<5	3.29	2	10	54	872	2.67	<10	0.49	1243	17	0.01	3	1080	38	10	<20	149	0.06	<10	18	<10	9	83
Resplit:																													
1	X05728	3.7	0.85	<5	100	<5	2.02	3	14	103	3413	4.18	<10	0.48	826	13	0.01	7	528	25	15	<20	151	0.02	<10	39	<10	5	66
Standard:																													
PB113A		10.9	0.33	55	60	<5	1.73	38	3	3	2271	1.10	<10	0.12	1578	68	0.02	3	100	5411	20	<20	94	0.01	<10	8	<10	<1	7003

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5696S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5697

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

29-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07192
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X12281	0.34	0.010
2	X12282	0.42	0.012
3	X12283	0.65	0.019
4	X12284	0.27	0.008
5	X12285	0.29	0.008
6	X12286	0.31	0.009
7	X12287	0.29	0.008
8	X12288	0.72	0.021
9	X12289	0.21	0.006
10	X12290	0.22	0.006
11	X12291	0.26	0.008
12	X12292	0.31	0.009
13	X12293	0.54	0.016
14	X12294	0.40	0.012
15	X12295	0.23	0.007
16	X12296	0.19	0.006
17	X12297	0.16	0.005
18	X12298	0.42	0.012
19	X12299	0.47	0.014
20	X12300	0.35	0.010
21	X12301	0.32	0.009
22	X12302	0.29	0.008
23	X12303	0.21	0.006
24	X12304	0.33	0.010
25	X12305	0.49	0.014
26	X12306	0.04	0.001
27	X12307	0.48	0.014
28	X12308	0.43	0.013
29	X12309	0.40	0.012

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5697 29-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X12310	0.32	0.009
31	X12311	0.23	0.007
32	X12312	0.98	0.029
33	X12313	0.27	0.008
34	X12314	0.33	<0.001
35	X12315	<0.03	<0.001

QC DATA:

Repeat:

1	X12281	0.30	0.009
10	X12290	0.23	0.007
19	X12299	0.53	0.015

Resplits:

1	X12281	0.33	0.010

Standard:

OXK48		3.43	0.100

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

29-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5697

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1


No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07192
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X12281	0.9	1.38	<5	85	<5	1.81	2	11	85	780	5.02	<10	1.16	945	13	0.03	6	1340	46	10	<20	123	0.02	<10	116	<10	3	91
2	X12282	1.6	1.28	<5	50	<5	1.44	2	12	112	1426	5.35	<10	0.96	776	10	0.02	5	1190	48	<5	<20	90	0.02	<10	89	<10	2	80
3	X12283	3.2	1.64	10	45	<5	1.29	2	12	100	2070	5.53	<10	1.42	984	13	0.01	6	1210	40	10	<20	74	0.02	<10	80	<10	2	98
4	X12284	2.3	1.24	5	45	<5	1.65	3	13	106	1130	4.67	<10	1.03	1022	12	0.02	5	980	48	<5	<20	118	0.02	<10	53	<10	2	181
5	X12285	4.8	1.23	5	35	<5	2.00	3	14	110	1315	5.02	<10	0.93	1140	14	0.02	7	1150	88	10	<20	103	0.02	<10	56	<10	1	112
6	X12286	1.6	1.34	<5	95	<5	2.33	2	10	112	796	4.19	<10	0.93	980	11	0.02	4	1220	40	<5	<20	121	0.02	<10	62	<10	2	107
7	X12287	1.8	1.32	<5	55	<5	2.09	2	14	146	852	5.41	<10	0.97	886	14	0.03	6	1170	42	5	<20	116	0.03	<10	105	<10	3	88
8	X12288	3.1	0.99	<5	50	<5	1.52	2	16	128	2708	6.37	<10	0.62	598	12	0.02	7	790	32	<5	<20	84	0.02	<10	84	<10	1	54
9	X12289	1.1	0.95	<5	45	<5	2.63	<1	13	128	747	4.49	<10	0.55	1092	14	0.02	6	1060	36	10	<20	141	0.02	<10	40	<10	1	67
10	X12290	1.7	0.74	<5	45	<5	1.95	2	18	112	829	6.37	<10	0.37	1009	14	0.01	7	940	56	<5	<20	172	0.02	<10	38	<10	<1	37
11	X12291	1.2	1.09	<5	65	<5	2.57	2	15	110	653	5.26	<10	0.70	1033	16	0.01	9	1090	34	15	<20	184	0.02	<10	63	<10	2	63
12	X12292	1.7	0.95	10	50	<5	2.00	2	12	111	794	5.09	<10	0.62	897	12	0.01	6	890	30	5	<20	150	0.02	<10	66	<10	1	59
13	X12293	7.2	0.87	50	40	<5	2.87	19	10	129	766	5.18	<10	0.99	1937	15	0.01	5	770	274	5	<20	139	0.03	<10	60	<10	1	1155
14	X12294	5.8	1.00	85	50	<5	3.87	8	10	94	1393	4.03	<10	2.57	3315	15	0.02	5	910	144	25	<20	137	0.03	<10	38	<10	4	447
15	X12295	2.3	1.19	15	40	<5	1.73	4	11	135	576	4.76	<10	1.16	1233	13	0.01	7	1050	52	15	<20	117	0.02	<10	49	<10	1	129
16	X12296	1.2	1.67	15	110	<5	2.04	1	9	123	473	3.75	<10	1.49	1205	13	0.01	4	1140	40	15	<20	181	0.02	<10	69	<10	4	75
17	X12297	1.0	1.92	10	70	<5	1.78	2	14	118	526	4.85	<10	1.82	1183	15	0.01	7	1150	48	25	<20	152	0.02	<10	76	<10	3	78
18	X12298	2.0	1.26	20	40	<5	1.63	2	14	114	1033	4.95	<10	1.25	1102	15	0.01	6	980	38	15	<20	121	0.02	<10	60	<10	2	56
19	X12299	2.3	1.24	5	50	<5	1.23	1	16	115	1171	6.99	<10	1.24	918	11	0.01	6	1080	36	<5	<20	84	0.03	<10	91	<10	1	53
20	X12300	1.3	2.07	<5	55	<5	1.54	2	13	136	672	6.75	<10	1.97	1208	15	0.01	7	1020	42	10	<20	114	0.03	<10	140	<10	<1	80
21	X12301	1.9	1.51	<5	50	<5	2.18	2	16	133	838	6.00	<10	1.56	1511	13	0.01	6	940	30	10	<20	139	0.03	<10	99	<10	<1	60
22	X12302	2.3	1.36	10	45	<5	1.98	3	13	112	770	5.27	<10	1.38	1423	17	0.01	10	1090	34	35	<20	133	0.02	<10	66	<10	1	83
23	X12303	3.4	1.33	15	50	<5	1.74	6	12	111	631	5.92	<10	1.37	1248	16	0.02	6	1160	66	10	<20	109	0.03	<10	62	<10	2	220
24	X12304	9.8	1.04	45	30	<5	2.23	2	12	124	786	5.29	<10	1.48	1927	12	0.02	6	1040	36	15	<20	95	0.03	<10	43	<10	2	55
25	X12305	19.5	0.85	85	50	<5	2.22	3	10	118	628	4.42	<10	1.65	2674	9	0.02	6	750	74	10	<20	132	0.04	<10	41	<10	4	71

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X12306	0.2	2.89	35	185	50	6.63	3	29	32	18	6.39	<10	2.19	2530	10	0.01	5	1120	58	30	<20	397	0.04	<10	80	<10	7	105
27	X12307	3.9	1.70	40	55	<5	1.99	3	14	125	1237	5.33	<10	1.34	1158	14	0.02	6	640	50	15	<20	116	0.03	<10	76	<10	2	65
28	X12308	2.3	1.16	<5	55	<5	1.44	2	13	130	1885	5.80	<10	0.79	529	12	0.02	7	630	30	10	<20	139	0.02	<10	141	<10	2	33
29	X12309	2.4	0.79	<5	60	<5	1.06	2	10	137	2138	4.56	<10	0.51	418	9	0.02	6	200	20	10	<20	123	0.01	<10	109	<10	<1	28
30	X12310	1.3	1.14	<5	85	<5	1.26	1	12	105	1527	4.99	<10	0.87	545	11	0.02	6	720	28	<5	<20	153	0.02	<10	140	<10	3	44
31	X12311	1.4	1.17	<5	70	<5	1.48	2	12	110	1396	5.58	<10	0.85	551	11	0.02	6	600	30	5	<20	182	0.02	<10	175	<10	3	38
32	X12312	3.6	1.37	55	65	<5	0.77	5	18	63	3311	4.28	20	0.55	283	221	0.03	14	460	148	40	<20	38	0.03	<10	49	<10	6	162
33	X12313	1.0	1.22	<5	60	<5	1.38	3	12	114	946	5.01	<10	0.84	484	13	0.02	8	830	28	20	<20	118	0.01	<10	103	<10	3	32
34	X12314	1.1	1.15	<5	65	<5	1.89	2	11	80	872	4.12	<10	0.70	675	13	0.02	6	1040	30	20	<20	143	0.01	<10	46	<10	5	31
35	X12315	<0.2	0.03	15	<5	15	>10	<1	2	5	3	0.03	<10	2.03	21	<1	<0.01	<1	60	10	15	<20	7206	<0.01	<10	4	<10	<1	<1
QC DATA:																													
Repeat:																													
1	X12281	0.7	1.41	<5	90	<5	1.81	2	11	88	777	5.05	<10	1.16	944	13	0.03	6	1310	46	10	<20	135	0.02	<10	120	<10	3	90
10	X12290	1.6	0.80	<5	50	<5	1.79	1	17	111	832	6.24	<10	0.38	995	13	0.01	6	910	58	<5	<20	167	0.03	<10	41	<10	<1	36
19	X12299	2.4	1.33	<5	50	<5	1.27	2	16	120	1198	7.18	<10	1.28	942	12	0.02	8	1120	38	5	<20	83	0.02	<10	98	<10	<1	54
Resplit:																													
1	X12281	0.9	1.52	<5	80	<5	1.72	3	13	85	803	5.29	<10	1.19	924	14	0.03	8	1350	54	10	<20	126	0.02	<10	119	<10	3	92
Standard:																													
PB113A		11.0	0.35	55	75	<5	1.86	41	3	6	2305	1.20	<10	0.13	1573	63	0.02	3	100	5500	30	<20	82	<0.01	<10	10	<10	<1	6905

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish



ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5682S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5698

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

5-Dec-07

No. of samples received: 34
Sample Type: Core
Project: KSM
Shipment #: 07191
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X12246	0.34	0.010
2	X12247	0.19	0.006
3	X12248	0.43	0.013
4	X12249	0.15	0.004
5	X12250	0.34	0.010
6	X12251	0.68	0.020
7	X12252	0.37	0.011
8	X12253	0.35	0.010
9	X12254	0.32	0.009
10	X12255	0.31	0.009
11	X12256	0.39	0.011
12	X12257	0.64	0.019
13	X12258	0.27	0.008
14	X12259	0.46	0.013
15	X12260	0.33	0.010
16	X12261	0.51	0.015
17	X12262	0.32	0.009
18	X12263	0.50	0.015
19	X12264	0.34	0.010
20	X12265	0.30	0.009
21	X12266	0.54	0.016
22	X12267	0.47	0.014
23	X12269	0.74	0.022
24	X12270	0.36	0.010
25	X12271	0.54	0.016
26	X12272	0.34	0.010
27	X12273	0.38	0.011
28	X12274	3.90	0.114
29	X12275	0.25	0.007

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5798 5-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X12276	0.48	0.014
31	X12277	0.24	0.007
32	X12278	0.36	0.010
33	X12279	0.93	0.027
34	X12280	<0.03	<0.001

QC DATA:

Repeat:

1	X12246	0.34	0.010
10	X12255	0.31	0.009
19	X12264	0.41	0.012

Resplits:

1	X12246	0.27	0.008

Standard:

SN26		8.53	0.249

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5698

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 34
Sample Type: Core
Project: KSM
Shipment #: 07191
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X12246	0.9	0.91	<5	85	<5	1.80	2	12	99	923	4.72	<10	0.77	1027	16	0.02	4	680	24	5	<20	123	0.02	<10	116	<10	<1	98
2	X12247	0.6	0.92	<5	220	<5	2.25	2	11	119	493	5.34	<10	0.85	1256	13	0.05	5	800	28	<5	<20	175	0.04	<10	202	<10	2	110
3	X12248	1.1	0.97	<5	115	<5	1.79	2	14	135	575	5.39	<10	0.85	1081	14	0.03	6	710	28	10	<20	104	0.03	<10	154	<10	1	114
4	X12249	0.3	1.00	<5	265	<5	2.36	3	11	90	382	5.60	<10	0.90	1323	17	0.02	8	860	34	20	<20	160	0.03	<10	155	<10	1	123
5	X12250	1.0	0.95	<5	130	<5	2.28	2	11	163	980	4.23	<10	0.72	1191	11	0.02	5	700	28	<5	<20	145	0.02	<10	92	<10	2	119
6	X12251	1.9	0.89	<5	70	<5	1.90	2	18	124	1452	5.25	<10	0.64	1019	14	0.01	6	580	24	<5	<20	91	0.02	<10	93	<10	<1	91
7	X12252	1.7	1.25	<5	70	<5	2.09	3	14	121	1346	5.57	<10	1.00	1132	13	0.01	6	800	32	10	<20	103	0.03	<10	91	<10	1	101
8	X12253	1.0	0.93	<5	270	<5	2.47	3	11	99	679	5.06	<10	0.80	1204	15	0.03	5	870	24	15	<20	151	0.03	<10	162	<10	2	135
9	X12254	2.1	0.75	<5	60	<5	2.03	3	11	148	1472	4.21	<10	0.62	956	9	0.02	5	550	24	5	<20	130	0.02	<10	94	<10	2	124
10	X12255	0.8	0.81	<5	75	<5	1.98	2	10	102	727	5.30	<10	0.68	877	12	0.02	5	770	22	10	<20	299	0.02	<10	142	<10	<1	110
11	X12256	1.3	1.04	5	90	<5	1.66	2	12	138	861	4.69	<10	0.73	1008	13	0.01	6	830	26	10	<20	86	0.02	<10	73	<10	1	106
12	X12257	1.4	1.16	10	65	<5	1.96	4	14	108	863	6.94	<10	0.86	1270	15	0.01	8	720	30	15	<20	117	0.03	<10	119	<10	<1	91
13	X12258	1.0	1.11	<5	60	<5	2.39	2	11	137	669	4.67	<10	0.83	1244	11	0.01	5	740	26	5	<20	155	0.02	<10	65	<10	1	95
14	X12259	1.6	1.36	30	45	<5	2.59	9	12	102	731	5.23	<10	1.17	1578	17	0.01	7	870	52	25	<20	132	0.03	<10	60	<10	<1	319
15	X12260	1.3	0.90	<5	55	<5	2.82	2	12	163	755	4.43	<10	0.69	1331	9	0.01	5	600	28	<5	<20	139	0.03	<10	63	<10	2	75
16	X12261	2.3	1.36	15	40	<5	3.19	2	11	96	1097	4.87	<10	1.37	1803	14	0.01	4	800	32	15	<20	135	0.03	<10	52	<10	2	82
17	X12262	2.3	1.03	<5	55	<5	2.48	2	13	131	1024	5.73	<10	0.99	1517	14	0.02	5	720	32	20	<20	102	0.03	<10	62	<10	2	63
18	X12263	2.6	1.01	<5	110	<5	1.70	3	12	90	1247	6.01	<10	0.74	1163	16	0.02	7	780	32	10	<20	111	0.02	<10	144	<10	<1	146
19	X12264	2.1	0.85	<5	75	<5	1.67	3	12	151	1272	5.26	<10	0.60	1039	12	0.02	9	670	24	10	<20	88	0.03	<10	105	<10	1	128
20	X12265	3.2	1.22	10	45	<5	1.00	3	22	61	2604	3.66	20	0.61	197	209	0.03	7	310	76	10	<20	49	0.03	<10	47	<10	6	270
21	X12266	2.2	0.97	<5	60	<5	1.86	3	14	89	1168	5.68	<10	0.72	1057	13	0.01	5	750	34	10	<20	90	0.02	<10	68	<10	<1	138
22	X12267	1.9	0.96	<5	60	<5	2.28	3	13	92	1185	5.48	<10	0.68	1144	14	0.02	7	840	30	20	<20	100	0.03	<10	83	<10	2	104
23	X12269	2.7	0.98	<5	55	<5	1.18	3	16	101	2084	5.67	<10	0.81	896	15	0.02	6	660	30	10	<20	68	0.03	<10	108	<10	2	118
24	X12270	1.3	1.09	<5	65	<5	1.87	3	14	101	1023	5.03	<10	0.99	1131	15	0.03	5	860	36	15	<20	79	0.03	<10	111	<10	2	103
25	X12271	1.6	0.80	<5	70	<5	1.61	2	10	106	1339	4.44	<10	0.64	929	10	0.02	4	560	24	<5	<20	81	0.02	<10	85	<10	2	69

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X12272	1.0	1.05	<5	135	<5	1.92	3	11	115	847	5.03	<10	0.92	1168	13	0.03	6	770	28	10	<20	136	0.03	<10	132	<10	2	153
27	X12273	2.0	1.13	<5	70	<5	2.06	2	12	89	918	4.85	<10	0.91	1094	15	0.02	4	730	26	10	<20	108	0.02	<10	88	<10	<1	88
28	X12274	12.2	1.21	5	50	<5	4.10	2	12	117	1296	4.94	<10	1.05	1832	11	0.01	6	630	30	15	<20	161	0.02	<10	56	<10	2	87
29	X12275	1.2	1.09	<5	60	<5	1.91	2	11	82	781	4.90	<10	0.80	920	14	0.01	5	830	26	10	<20	114	0.02	<10	70	<10	1	84
30	X12276	1.3	1.09	<5	70	<5	2.28	2	12	112	1160	4.96	<10	0.83	1024	13	0.02	5	830	28	5	<20	132	0.02	<10	85	<10	2	85
31	X12277	0.9	1.04	<5	75	<5	2.03	2	11	92	886	4.94	<10	0.80	983	12	0.01	5	660	24	5	<20	116	0.02	<10	78	<10	<1	82
32	X12278	0.8	1.15	<5	55	80	2.00	2	14	101	755	4.91	<10	0.91	1050	14	0.02	5	1000	48	10	<20	125	0.05	<10	78	<10	7	104
33	X12279	<0.2	0.86	1595	90	35	0.94	6	31	24	52	4.83	<10	1.97	641	12	0.19	122	1010	24	15	<20	52	0.06	<10	23	<10	9	70
34	X12280	<0.2	0.13	10	<5	<5	>10	<1	2	9	<1	0.20	<10	1.75	40	<1	0.03	<1	70	6	<5	<20	6527	0.02	<10	10	<10	<1	<1
QC DATA:																													
Repeat:																													
1	X12246	1.1	0.93	<5	70	<5	1.78	2	12	102	911	4.73	<10	0.76	1015	17	0.02	4	670	26	10	<20	132	0.02	<10	120	<10	<1	97
10	X12255	0.9	0.83	<5	70	<5	1.95	2	10	104	722	5.30	<10	0.68	863	12	0.02	4	740	22	5	<20	320	0.03	<10	146	<10	<1	108
19	X12264	1.9	0.88	<5	80	<5	1.70	3	12	159	1298	5.35	<10	0.60	1054	11	0.02	6	690	24	5	<20	94	0.03	<10	109	<10	1	130
Resplit:																													
1	X12246	1.1	0.85	<5	65	<5	1.78	3	12	101	972	4.63	<10	0.71	1012	16	0.02	10	590	24	5	<20	133	0.02	<10	112	<10	<1	92
Standard:																													
PB113A		10.9	0.29	40	55	<5	1.72	40	2	6	2260	1.11	<10	0.10	1449	70	0.02	3	90	5608	20	<20	86	<0.01	<10	7	<10	<1	7103

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
dl/5698S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5699

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM :
Shipment #: 07209
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05868	0.49	0.014
2	X05869	1.87	0.055
3	X05870	1.62	0.047
4	X05871	0.49	0.014
5	X05872	0.54	0.016
6	X05873	0.78	0.023
7	X05874	1.53	0.045
8	X05875	0.79	0.023
9	X05876	0.53	0.015
10	X05877	1.83	0.053
11	X05878	0.59	0.017
12	X05879	0.43	0.013
13	X05880	0.63	0.018
14	X05881	0.70	0.020
15	X05882	0.50	0.015
16	X05883	0.38	0.011
17	X05884	0.48	0.014
18	X05885	0.43	0.013
19	X05886	<0.03	<0.001
20	X05887	0.57	0.017
21	X05888	0.51	0.015
22	X05889	0.73	0.021
23	X05890	0.63	0.018
24	X05891	0.62	0.018
25	X05892	1.03	0.030
26	X05893	0.28	0.008
27	X05894	0.43	0.013
28	X05895	0.49	0.014

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS2007-5699 4-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	X05896	0.46	0.013
30	X05897	0.46	0.013
31	X05898	0.47	0.014
32	X05899	0.57	0.017
33	X05900	0.51	0.015
34	X05901	0.34	0.010
35	X05902	0.35	0.010

QC DATA:

Repeat:

1	X05868	0.51	0.015
2	X05869	1.83	0.053
3	X05870	1.66	0.048
7	X05874	1.57	0.046
11	X05878	0.57	0.017
20	X05887	0.55	0.016
25	X05892	1.01	0.029

Resplits:

1	X05868	0.54	0.016

Standard:

OXK48		3.52	0.103

AU: 30g FA/AA-Finish

JJ/kk
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5699

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07209
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05868	1.6	0.95	20	95	<5	2.36	2	10	53	1388	3.75	<10	0.64	860	46	0.02	3	1610	22	<5	<20	103	0.03	<10	21	<10	6	63
2	X05869	2.4	0.73	115	40	<5	1.93	3	9	70	1544	3.92	<10	0.44	732	19	0.01	2	1330	26	5	<20	85	0.01	<10	15	<10	5	65
3	X05870	1.8	0.93	60	55	<5	2.23	2	10	68	1455	4.12	<10	0.65	823	19	0.02	3	1440	14	<5	<20	125	0.02	<10	26	<10	5	78
4	X05871	1.8	1.03	25	70	<5	3.36	2	12	55	1474	4.37	<10	0.73	1080	19	0.02	3	1480	16	<5	<20	209	0.02	<10	26	<10	6	72
5	X05872	1.9	1.16	25	95	<5	2.90	2	12	84	1445	4.12	<10	0.83	1113	23	0.02	4	1540	10	<5	<20	170	0.02	<10	25	<10	6	81
6	X05873	2.6	1.07	15	120	<5	2.84	2	12	83	2084	4.84	<10	0.76	995	29	0.03	3	1510	16	<5	<20	198	0.03	<10	41	<10	7	76
7	X05874	4.5	1.08	15	75	<5	2.04	3	11	110	4780	4.94	<10	0.80	805	19	0.03	4	1400	22	<5	<20	127	0.03	<10	43	<10	6	87
8	X05875	2.6	1.14	15	75	<5	2.57	4	10	74	2589	4.72	<10	0.89	1004	19	0.03	3	1420	36	<5	<20	170	0.03	<10	44	<10	6	191
9	X05876	2.0	0.88	15	90	<5	2.94	2	10	66	1810	3.58	<10	0.55	1164	25	0.02	3	1540	16	<5	<20	187	0.04	<10	28	<10	7	67
10	X05877	4.0	1.03	35	40	<5	1.01	3	18	57	8542	4.05	20	0.56	204	590	0.04	63	600	52	20	<20	61	0.04	<10	35	<10	8	75
11	X05878	1.8	0.94	15	60	<5	2.07	2	11	102	1386	4.53	<10	0.72	935	17	0.03	3	1290	18	<5	<20	151	0.04	<10	45	<10	5	80
12	X05879	1.6	0.97	20	55	<5	2.27	2	10	77	1174	3.88	<10	0.71	1067	18	0.03	3	1380	16	<5	<20	180	0.04	<10	33	<10	5	102
13	X05880	1.7	0.96	20	90	<5	2.30	2	10	90	1650	4.50	<10	0.69	1150	18	0.03	3	1410	14	<5	<20	147	0.04	<10	40	<10	5	100
14	X05881	2.3	0.83	20	50	<5	2.96	2	12	89	1740	3.94	<10	0.52	1227	22	0.02	3	1330	22	<5	<20	160	0.02	<10	20	<10	6	79
15	X05882	3.8	0.75	25	40	<5	2.96	19	11	80	1790	3.90	<10	0.49	1193	13	0.02	3	1240	334	<5	<20	155	0.02	<10	22	<10	6	1263
16	X05883	1.6	0.82	15	80	<5	3.14	2	9	75	1343	3.52	<10	0.44	1108	18	0.02	3	1420	12	<5	<20	223	<0.01	<10	26	<10	6	57
17	X05884	1.5	1.04	25	65	<5	3.85	2	10	83	1281	4.40	<10	0.69	1617	15	0.02	3	1510	18	<5	<20	209	0.02	<10	30	<10	7	80
18	X05885	1.2	0.98	20	140	<5	3.07	2	9	76	1082	3.98	<10	0.67	1324	16	0.02	3	1520	16	<5	<20	204	0.03	<10	36	<10	6	85
19	X05886	<0.2	0.19	<5	<5	<5	>10	<1	<1	2	3	0.08	<10	1.43	24	<1	0.01	<1	80	<2	<5	<20	6248	<0.01	<10	<1	<10	<1	3
20	X05887	1.6	0.91	15	115	<5	2.17	2	10	87	1612	4.10	<10	0.66	963	22	0.02	3	1400	10	<5	<20	150	0.03	<10	37	<10	6	83
21	X05888	1.3	1.03	15	100	<5	3.38	2	11	78	1507	4.14	<10	0.85	1296	21	0.04	3	1450	12	<5	<20	279	0.06	<10	57	<10	6	85
22	X05889	1.6	0.94	20	75	<5	1.85	2	10	81	1778	4.31	<10	0.70	891	13	0.02	3	1320	12	<5	<20	103	0.03	<10	39	<10	6	69
23	X05890	1.8	1.01	15	70	<5	2.06	2	9	100	1840	4.76	<10	0.79	921	12	0.03	3	1330	10	<5	<20	152	0.04	<10	55	<10	6	73
24	X05891	1.9	0.97	15	120	<5	2.55	2	9	84	1939	4.91	<10	0.74	1022	16	0.03	3	1330	10	<5	<20	171	0.04	<10	57	<10	6	74
25	X05892	2.6	1.34	20	65	<5	3.39	3	12	53	2665	5.26	<10	1.11	1531	13	0.02	2	1360	10	<5	<20	176	0.01	<10	51	<10	6	86

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05893	0.6	1.92	20	90	<5	6.30	2	12	44	592	5.80	<10	1.83	2397	8	0.03	2	1450	6	<5	<20	340	0.03	<10	54	<10	6	104
27	X05894	1.6	1.71	50	55	<5	2.72	2	18	72	1039	5.62	<10	1.31	1564	21	0.02	4	1660	14	<5	<20	99	<0.01	<10	25	<10	6	121
28	X05895	1.5	1.60	45	65	<5	3.63	2	18	72	977	4.97	<10	1.11	1722	14	0.02	4	1530	12	5	<20	165	<0.01	<10	26	<10	5	119
29	X05896	1.5	1.04	25	65	<5	3.20	2	10	63	1216	3.37	<10	0.68	1259	17	0.01	4	1640	12	<5	<20	171	<0.01	<10	20	<10	5	75
30	X05897	1.4	1.09	20	80	<5	3.75	2	10	61	1319	3.62	<10	0.71	1366	17	0.01	3	1490	8	<5	<20	242	<0.01	<10	20	<10	5	72
31	X05898	1.4	1.09	30	70	<5	5.58	2	9	56	886	3.31	<10	0.84	1997	19	0.01	3	1320	8	<5	<20	245	<0.01	<10	21	<10	7	67
32	X05899	1.6	1.19	40	45	<5	3.57	2	14	82	1211	4.97	<10	0.95	1579	13	0.02	3	1320	14	<5	<20	201	<0.01	<10	27	<10	6	73
33	X05900	1.3	1.46	20	85	<5	1.56	2	11	64	1395	4.99	<10	1.15	1128	21	0.02	3	1610	6	<5	<20	103	<0.01	<10	33	<10	5	96
34	X05901	1.4	1.36	20	60	<5	2.38	2	11	64	1166	4.76	<10	1.09	1272	18	0.02	3	1540	6	<5	<20	170	<0.01	<10	35	<10	6	86
35	X05902	1.3	1.35	20	65	<5	2.52	2	12	63	1271	4.22	<10	1.09	1311	21	0.02	3	1590	8	<5	<20	174	<0.01	<10	31	<10	6	83
QC DATA:																													
Repeat:																													
1	X05868	1.7	0.98	20	100	<5	2.35	2	10	54	1383	3.78	<10	0.64	865	48	0.02	3	1630	20	<5	<20	105	0.03	<10	22	<10	6	60
11	X05878	1.9	1.04	15	65	<5	2.11	3	12	104	1398	4.71	<10	0.74	963	14	0.04	4	1310	18	<5	<20	160	0.05	<10	47	<10	6	87
Resplit:																													
1	X05868	1.6	1.06	20	95	<5	2.36	2	11	49	1349	3.98	<10	0.66	859	38	0.02	3	1690	18	<5	<20	111	0.03	<10	22	<10	7	64
Standard:																													
PB113A		11.2	0.27	50	65	<5	1.69	34	2	<1	2331	1.11	<10	0.11	1597	67	0.02	1	90	5612	5	<20	87	0.01	<10	5	<10	1	7052

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
dl/n5699S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5700R

Seabridge Gold Inc. *Revised* 29-Nov-07
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07210
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05903	0.34	0.010
2	X05904	0.26	0.008
3	X05905	0.39	0.011
4	X05906	0.43	0.013
5	X05907	<0.03	<0.001
6	X05908	0.46	0.013
7	X05909	0.41	0.012
8	X05910	0.43	0.013
9	X05911	0.44	0.013
10	X05912	0.43	0.013
11	X05913	0.44	0.013
12	X05914	0.32	0.009
13	X05915	0.48	0.014
14	X05916	0.32	0.009
15	X05917	0.81	0.024
16	X05918	0.46	0.013
17	X05919	2.77	0.081
18	X05920	0.54	0.016
19	X05921	0.46	0.013
20	X05922	0.46	0.013
21	X05923	0.44	0.013
22	X05924	0.43	0.013
23	X05925	0.46	0.013
24	X05926	0.41	0.012
25	X05927	0.81	0.024
26	X05928	0.59	0.017

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5700R 29-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	X05929	1.85	0.054
28	X05930	0.53	0.015
29	X05931	0.45	0.013
30	X05932	0.29	0.008
31	X05933	0.56	0.016
32	X05934	0.33	0.010
33	X05935	0.33	0.010
34	X05936	<0.03	<0.001
35	X05937	0.03	0.001
QC DATA:			
Repeat:			
1	X05903	0.34	0.010
13	X05915	0.49	0.014
10	X05912	0.43	0.013
15	X05917	0.79	0.023
17	X05919	2.84	0.083
19	X05921	0.42	0.012
Resplits:			
1	X05903	0.38	0.011
Standard:			
OXK48		3.54	0.103

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/sa
XLS/07

30-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5700

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07210
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05903	1.1	1.20	<5	90	<5	2.63	2	13	60	1106	4.57	<10	0.85	1026	27	0.02	4	1490	32	5	<20	207	0.03	<10	49	<10	5	69
2	X05904	1.1	1.30	<5	75	<5	2.97	2	14	71	957	4.60	<10	1.05	1155	22	0.03	5	1450	28	15	<20	253	0.03	<10	63	<10	4	69
3	X05905	1.1	1.33	<5	60	<5	2.68	2	14	84	1151	4.57	<10	1.08	1139	25	0.02	6	1340	30	15	<20	242	0.02	<10	61	<10	5	68
4	X05906	1.8	1.16	<5	65	<5	3.28	3	14	95	1613	4.73	<10	0.83	1301	27	0.02	9	1110	30	30	<20	242	0.01	<10	41	<10	4	56
5	X05907	<0.2	0.03	20	<5	<5	>10	<1	<1	2	2	0.03	<10	2.19	30	<1	<0.01	<1	60	8	15	<20	7160	<0.01	<10	3	<10	<1	2
6	X05908	1.8	1.43	15	70	<5	3.16	2	15	92	1303	4.02	<10	1.03	1483	26	<0.01	7	1440	38	15	<20	213	0.03	<10	30	<10	6	77
7	X05909	1.8	1.30	15	65	<5	3.00	1	14	96	1260	3.88	<10	0.85	1318	28	0.01	5	1580	28	15	<20	221	0.02	<10	33	<10	5	67
8	X05910	1.5	1.24	5	105	<5	2.99	2	12	111	1309	3.66	<10	0.77	1365	28	0.01	7	1560	28	15	<20	274	0.01	<10	33	<10	4	63
9	X05911	1.3	1.95	15	125	<5	2.45	1	12	106	1291	4.23	<10	1.52	1530	23	0.01	6	1520	40	20	<20	227	0.03	<10	35	<10	5	91
10	X05912	1.8	1.72	5	50	<5	1.64	1	13	108	1372	4.31	<10	1.54	1192	19	<0.01	6	1390	40	15	<20	140	0.02	<10	34	<10	4	78
11	X05913	1.7	2.00	10	100	<5	3.08	1	14	92	1234	4.62	<10	1.68	1792	26	0.02	6	1580	40	20	<20	287	0.03	<10	46	<10	5	97
12	X05914	1.5	1.81	5	90	<5	3.17	2	14	75	1131	4.47	<10	1.50	1755	29	0.02	6	1520	40	20	<20	279	0.03	<10	42	<10	5	89
13	X05915	1.4	1.45	20	55	<5	2.83	2	16	132	1023	4.77	<10	1.11	1481	20	<0.01	7	1180	38	15	<20	274	0.03	<10	33	<10	4	69
14	X05916	1.4	1.40	5	115	<5	3.12	2	14	126	1127	4.62	<10	1.03	1476	18	0.02	6	1180	36	15	<20	361	0.03	<10	43	<10	5	90
15	X05917	2.6	1.63	35	55	<5	1.56	2	17	110	1398	5.69	<10	1.20	922	21	<0.01	6	1330	46	10	<20	135	0.02	<10	32	<10	3	78
16	X05918	2.0	2.03	15	80	<5	1.24	1	14	81	1222	4.63	<10	1.65	928	30	<0.01	5	1570	46	15	<20	121	0.02	<10	44	<10	4	87
17	X05919	2.6	1.90	10	55	<5	2.88	2	15	115	1086	5.08	<10	1.70	1649	22	<0.01	6	1220	40	15	<20	233	0.03	<10	42	<10	3	77
18	X05920	1.8	2.10	15	75	<5	2.57	1	17	101	1618	4.98	<10	2.32	1723	23	0.01	6	1300	48	25	<20	203	0.03	<10	57	<10	7	80
19	X05921	1.3	1.82	10	65	<5	1.91	1	13	110	1433	4.65	<10	1.74	1309	24	0.02	5	1320	42	15	<20	183	0.02	<10	55	<10	3	73
20	X05922	1.3	1.86	<5	75	<5	1.52	1	13	122	1316	4.42	<10	1.73	1247	21	0.02	6	1280	42	15	<20	158	0.03	<10	46	<10	4	79
21	X05923	1.9	1.80	5	70	<5	1.82	2	16	107	1649	4.94	<10	1.57	1233	27	0.02	6	1540	40	15	<20	170	0.03	<10	49	<10	5	81
22	X05924	1.7	1.53	15	70	<5	1.99	2	17	119	1247	5.18	<10	1.25	1109	22	0.02	7	1210	38	15	<20	199	0.03	<10	65	<10	4	81
23	X05925	1.7	1.64	<5	80	<5	1.76	2	16	125	1417	4.88	<10	1.37	1106	27	0.03	7	1340	36	15	<20	188	0.02	<10	64	<10	5	75
24	X05926	1.5	1.49	<5	145	<5	1.94	1	14	104	1430	4.70	<10	1.36	1169	22	0.05	5	1380	32	10	<20	244	0.03	<10	93	<10	5	76
25	X05927	1.6	1.80	<5	90	<5	2.48	2	14	118	1475	5.10	<10	1.96	1697	25	0.03	6	1210	38	20	<20	216	0.03	<10	77	<10	4	79

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007-5700 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05928	1.8	1.37	<5	100	<5	1.80	2	15	111	1832	5.44	<10	1.18	932	20	0.04	7	1250	30	20	<20	179	0.04	<10	98	<10	3	81
27	X05929	3.9	1.17	25	55	<5	1.14	3	24	62	8397	4.28	20	0.69	220	635	0.05	63	230	74	30	<20	55	0.02	<10	50	<10	6	79
28	X05930	1.7	1.26	<5	135	<5	2.00	2	15	104	1607	5.57	<10	1.10	1077	20	0.04	6	1260	28	10	<20	203	0.03	<10	101	<10	4	95
29	X05931	1.0	1.25	<5	250	<5	2.02	3	13	101	1249	4.92	<10	1.03	982	26	0.05	9	1380	26	30	<20	212	0.02	<10	98	<10	3	76
30	X05932	0.9	1.28	<5	250	<5	2.04	1	12	75	995	4.32	<10	1.04	1024	22	0.04	4	1350	28	5	<20	220	0.03	<10	86	<10	5	74
31	X05933	2.3	1.89	<5	80	<5	2.14	2	15	100	1772	5.38	<10	1.76	1538	20	0.02	7	1280	38	10	<20	167	0.03	<10	86	<10	4	91
32	X05934	1.5	1.82	<5	70	<5	1.54	2	16	108	1180	4.95	<10	1.58	1103	33	0.03	7	1470	38	15	<20	132	0.03	<10	79	<10	3	79
33	X05935	1.1	1.64	<5	475	<5	1.94	1	14	79	1368	5.39	<10	1.43	979	34	0.04	2	1610	34	<5	<20	197	0.08	<10	125	<10	6	90
34	X05936	<0.2	3.38	<5	365	55	4.41	2	36	53	8	7.76	<10	3.61	1462	9	0.03	5	1110	58	25	<20	277	0.23	<10	230	<10	11	90
35	X05937	<0.2	3.85	5	250	85	4.59	3	41	60	10	8.00	<10	4.15	1414	10	0.03	5	1080	70	35	<20	288	0.25	<10	258	<10	11	92
QC DATA:																													
Repeat:																													
1	X05903	1.2	1.24	<5	90	<5	2.61	2	13	63	1100	4.56	<10	0.86	1025	24	0.02	4	1500	32	10	<20	211	0.03	<10	51	<10	4	68
10	X05912	1.6	1.74	5	55	<5	1.62	2	13	112	1331	4.27	<10	1.52	1179	20	0.01	7	1380	42	20	<20	140	0.02	<10	36	<10	5	78
19	X05921	1.4	1.90	5	75	<5	1.94	2	13	116	1450	4.73	<10	1.78	1322	26	0.02	6	1340	42	25	<20	190	0.02	<10	59	<10	3	74
Resplit:																													
1	X05903	1.2	1.27	<5	75	<5	2.73	2	14	55	1049	4.74	<10	0.91	1120	25	0.02	5	1560	32	5	<20	210	0.03	<10	52	<10	5	70
Standard:																													
PB113A		10.9	0.33	50	65	<5	1.90	39	3	6	2257	1.18	<10	0.12	1586	70	0.02	2	100	5654	20	<20	105	0.01	<10	9	<10	<1	6874

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5696S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5701

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

29-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07201
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X14001	0.59	0.017
2	X14002	0.69	0.020
3	X14003	1.01	0.029
4	X14004	0.96	0.028
5	X14005	0.67	0.020
6	X14006	0.67	0.020
7	X14007	0.49	0.014
8	X14008	0.78	0.023
9	X14009	0.59	0.017
10	X14010	0.67	0.020
11	X14011	0.73	0.021
12	X14012	0.70	0.020
13	X14013	0.84	0.024
14	X14014	0.44	0.013
15	X14015	1.05	0.031
16	X14016	0.83	0.024
17	X14017	0.93	0.027
18	X14018	1.04	0.030
19	X14019	0.83	0.024
20	X14020	0.87	0.025
21	X14021	0.66	0.019
22	X14022	0.94	0.027
23	X14023	0.72	0.021
24	X14024	0.88	0.026
25	X14025	0.77	0.022
26	X14026	0.81	0.024
27	X14027	0.71	0.021
28	X14028	0.76	0.022
29	X14029	0.60	0.017

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5701 29-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X14030	0.26	0.008
31	X14031	<0.03	<0.001
32	X14032	0.07	0.002
33	X14033	0.86	0.025
34	X14034	0.83	0.024
35	X14035	0.30	0.009

QC DATA:

Repeat:

1	X14001	0.52	0.015
10	X14010	0.67	0.020
19	X14019	0.81	0.024

Resplits:

1	X14001	0.58	0.017

Standard:

OXK48		3.57	0.104

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5701

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07201
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X14001	1.5	1.14	<5	65	<5	1.95	5	15	70	1189	4.32	<10	1.32	1723	80	0.01	5	1190	112	15	<20	39	0.02	<10	19	<10	3	341
2	X14002	1.8	1.10	<5	65	<5	1.16	3	16	108	1221	5.08	<10	0.98	1265	136	0.01	6	1040	130	15	<20	47	0.02	<10	18	<10	2	322
3	X14003	1.8	1.21	<5	60	<5	0.68	3	18	115	1288	5.79	<10	0.84	786	161	0.01	9	1470	60	20	<20	43	0.02	<10	27	<10	1	234
4	X14004	1.5	1.01	<5	55	<5	0.65	3	13	100	1653	5.57	<10	0.62	972	96	0.01	9	1420	48	20	<20	44	0.01	<10	26	<10	<1	178
5	X14005	1.3	1.78	<5	65	<5	0.60	2	19	112	1097	6.30	<10	1.24	1178	92	<0.01	9	1780	54	20	<20	30	0.02	<10	39	<10	<1	297
6	X14006	1.8	0.89	<5	55	<5	0.78	2	18	98	1293	6.04	<10	0.56	1512	130	0.01	7	1530	72	5	<20	33	0.03	<10	25	<10	<1	180
7	X14007	2.0	0.79	5	55	<5	0.56	3	16	127	1185	5.80	<10	0.44	808	111	0.01	8	1260	100	5	<20	32	0.02	<10	20	<10	<1	219
8	X14008	2.0	0.79	15	55	<5	0.58	10	17	122	1356	5.88	<10	0.51	980	108	0.01	8	1020	162	15	<20	41	0.02	<10	17	<10	<1	565
9	X14009	2.1	0.87	10	50	<5	0.70	4	17	142	1343	5.62	<10	0.61	1165	187	0.01	10	980	106	15	<20	33	0.02	<10	20	<10	<1	315
10	X14010	2.6	1.14	15	55	<5	0.72	4	14	129	1440	4.60	<10	0.93	1248	130	0.01	8	890	116	15	<20	41	0.02	<10	20	<10	<1	379
11	X14011	1.9	0.86	10	55	<5	0.61	4	13	149	1628	4.59	<10	0.58	944	205	0.01	8	890	258	10	<20	36	0.02	<10	18	<10	<1	303
12	X14012	1.4	1.38	20	55	<5	0.48	2	14	99	1264	4.71	<10	1.01	1372	129	<0.01	6	1150	84	10	<20	31	0.02	<10	24	<10	<1	276
13	X14013	1.6	1.52	5	70	<5	0.81	2	14	149	1230	4.57	<10	1.24	2040	148	<0.01	8	1040	92	15	<20	45	0.03	<10	26	<10	2	332
14	X14014	1.3	1.11	5	60	<5	0.76	3	14	157	1050	4.93	<10	0.84	1269	76	0.01	9	950	106	10	<20	38	0.02	<10	20	<10	<1	310
15	X14015	1.8	1.32	10	60	<5	0.58	4	15	156	1112	4.97	<10	0.95	1527	138	0.01	11	1050	92	25	<20	44	0.02	<10	25	<10	1	358
16	X14016	1.8	1.14	15	65	<5	1.72	2	12	126	1374	3.91	<10	1.29	2172	141	<0.01	7	830	124	20	<20	60	0.02	<10	22	<10	<1	235
17	X14017	1.3	1.76	15	80	<5	1.68	2	14	141	1230	4.82	<10	1.67	2634	564	0.01	7	960	104	20	<20	85	0.04	<10	32	<10	2	298
18	X14018	2.0	2.09	10	70	<5	1.26	2	13	117	1630	4.94	<10	1.77	2387	135	<0.01	8	980	130	15	<20	57	0.03	<10	33	<10	<1	407
19	X14019	3.3	0.96	20	55	<5	0.89	17	20	177	1817	5.15	<10	0.74	1532	292	0.01	10	1120	422	15	<20	47	0.02	<10	21	<10	<1	940
20	X14020	1.7	0.92	15	45	<5	0.68	3	12	151	1322	3.57	<10	0.67	917	174	<0.01	6	800	118	5	<20	32	0.01	<10	17	<10	<1	255
21	X14021	1.7	0.95	5	60	<5	0.79	6	13	140	1260	3.85	<10	0.72	1075	97	0.01	15	990	110	45	<20	52	<0.01	<10	22	<10	3	259
22	X14022	1.9	2.55	25	100	<5	0.70	<1	16	119	1444	5.47	<10	1.81	1386	99	<0.01	8	1450	86	<5	<20	40	0.03	<10	47	<10	2	440
23	X14023	2.8	1.29	5	55	<5	0.97	4	17	123	1626	5.04	<10	1.03	1475	76	<0.01	10	1200	118	15	<20	54	0.02	<10	27	<10	1	341
24	X14024	2.1	1.77	5	65	<5	0.80	2	17	112	1372	5.32	<10	1.34	1609	83	<0.01	8	1220	84	20	<20	54	0.03	<10	33	<10	1	311
25	X14025	2.2	0.75	20	55	<5	1.01	6	15	155	1446	4.82	<10	0.61	1188	120	0.01	11	1020	182	<5	<20	55	0.02	<10	17	<10	<1	422

ICP CERTIFICATE OF ANALYSIS AS 2007-5701

Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X14026	1.9	1.30	15	60	<5	1.45	7	15	124	1681	4.89	<10	1.22	1913	161	<0.01	12	1350	154	25	<20	77	0.02	<10	24	<10	3	468
27	X14027	1.9	1.36	5	60	<5	1.23	7	13	132	1375	4.62	<10	1.15	1849	105	0.01	12	1220	292	10	<20	57	0.03	<10	24	<10	2	539
28	X14028	2.0	1.57	<5	60	<5	0.97	12	18	104	1577	5.34	<10	1.22	1681	109	<0.01	12	1340	156	10	<20	55	0.03	<10	27	<10	<1	784
29	X14029	1.6	1.06	10	55	<5	0.79	2	13	149	1571	4.51	<10	0.88	1289	182	0.01	13	720	68	15	<20	50	0.02	<10	16	<10	<1	264
30	X14030	1.9	0.38	40	40	<5	0.57	4	10	164	1291	4.43	<10	0.25	536	115	0.01	13	360	94	10	<20	38	<0.01	<10	6	<10	<1	187
31	X14031	<0.2	0.04	25	<5	<5	>10	<1	1	3	3	0.03	<10	2.12	21	<1	<0.01	<1	60	8	<5	<20	5991	<0.01	<10	4	<10	<1	<1
32	X14032	0.2	0.99	65	135	70	0.34	5	70	261	403	>10	20	0.19	461	121	0.05	412	100	144	5	<20	9	0.05	<10	29	<10	<1	408
33	X14033	1.8	1.20	10	65	<5	1.12	2	15	157	1434	4.87	<10	1.00	1677	127	<0.01	23	970	114	10	<20	55	0.03	<10	18	<10	2	218
34	X14034	1.4	1.36	10	60	<5	1.42	2	12	161	1420	4.79	<10	1.25	2029	113	<0.01	23	760	50	15	<20	58	0.03	<10	19	<10	<1	238
35	X14035	3.0	1.29	30	85	<5	1.08	3	23	61	2594	3.81	20	0.67	209	215	0.03	9	540	80	15	<20	63	0.05	<10	52	<10	7	291
QC DATA:																													
Repeat:																													
1	X14001	1.6	1.13	<5	65	<5	1.94	5	15	69	1199	4.26	<10	1.32	1709	78	0.01	4	1180	108	15	<20	45	0.02	<10	19	<10	3	334
10	X14010	2.4	1.13	25	50	<5	0.71	4	15	129	1400	4.56	<10	0.91	1230	126	<0.01	7	880	116	10	<20	39	0.02	<10	20	<10	<1	379
19	X14019	3.2	0.93	20	60	<5	0.88	16	20	170	1773	5.07	<10	0.72	1503	282	0.01	9	1150	416	10	<20	50	0.02	<10	21	<10	<1	938
Resplit:																													
1	X14001	1.7	1.09	5	60	<5	2.04	5	15	77	1122	4.35	<10	1.31	1777	77	0.01	6	1140	110	20	<20	43	0.03	<10	19	<10	3	347
Standard:																													
PB113A		10.9	0.32	60	75	<5	1.78	39	3	6	2273	1.16	<10	0.13	1557	74	0.02	4	100	5560	20	<20	99	<0.01	<10	10	<10	<1	6961

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5696S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5702

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

3-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07195
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05588	1.86	0.054
2	X05589	1.01	0.029
3	X05590	0.77	0.022
4	X05591	0.99	0.029
5	X05592	0.61	0.018
6	X05593	0.75	0.022
7	X05594	0.88	0.026
8	X05595	0.64	0.019
9	X05596	0.75	0.022
10	X05597	1.01	0.029
11	X05598	0.91	0.027
12	X05599	1.54	0.045
13	X05600	1.58	0.046
14	X05601	0.75	0.022
15	X05602	1.20	0.035
16	X05603	0.89	0.026
17	X05604	0.88	0.026
18	X05605	1.12	0.033
19	X05606	0.96	0.028
20	X05607	0.64	0.019
21	X05608	0.63	0.018
22	X05609	0.75	0.022
23	X05610	0.83	0.024
24	X05611	<0.03	<0.001
25	X05612	0.88	0.026
26	X05613	0.86	0.025
27	X05614	0.75	0.022
28	X05615	0.88	0.026
29	X05616	1.01	0.029

ECO-TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5702 3-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X05617	1.06	0.031
31	X05618	1.16	0.034
32	X05619	1.24	0.036
33	X05620	0.94	0.027
34	X05621	0.86	0.025
35	X05622	0.77	0.022

QC DATA:

Repeat:

1	X05588	1.85	0.054
10	X05597	1.11	0.032
12	X05599	1.53	0.045
13	X05600	1.51	0.044
19	X05606	0.97	0.028
26	X05613	0.84	0.024
31	X05618	1.11	0.032
32	X05619	1.16	0.034

Resplits:

1	X05588	1.97	0.057

Standard:

OXK48		3.51	0.102

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

30-Nov-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5702

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07195
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05588	6.6	0.72	115	50	<5	0.43	3	14	103	3059	6.29	<10	0.23	284	24	<0.01	5	840	44	<5	<20	36	0.01	<10	18	<10	<1	35
2	X05589	4.0	1.55	45	55	<5	0.92	2	14	94	1946	5.33	<10	0.77	916	29	<0.01	6	1120	42	15	<20	93	0.02	<10	28	<10	1	69
3	X05590	3.5	1.40	15	60	<5	1.32	2	15	106	1874	4.67	<10	0.87	829	25	<0.01	6	1210	40	10	<20	158	0.02	<10	33	<10	3	69
4	X05591	3.7	1.20	60	70	<5	0.84	4	19	63	3284	4.07	20	0.57	307	221	0.03	13	420	154	35	<20	39	0.04	<10	51	<10	8	166
5	X05592	3.0	1.59	10	95	<5	1.17	1	12	80	1634	4.99	<10	1.06	949	31	<0.01	6	1310	40	10	<20	142	0.02	<10	38	<10	3	76
6	X05593	3.6	1.58	10	80	<5	1.17	1	13	87	1821	5.09	<10	1.03	917	27	<0.01	6	1280	42	15	<20	158	0.02	<10	39	<10	4	75
7	X05594	4.3	1.34	<5	65	<5	1.23	1	15	128	2427	4.90	<10	1.00	1010	41	0.01	6	1040	38	10	<20	136	0.02	<10	36	<10	3	60
8	X05595	2.5	1.53	<5	90	<5	1.65	1	13	90	1494	4.73	<10	1.34	1416	26	<0.01	5	1280	38	10	<20	160	0.03	<10	32	<10	4	68
9	X05596	4.5	0.98	10	50	<5	1.00	1	19	116	2204	4.60	<10	0.74	962	25	<0.01	5	800	40	10	<20	94	0.02	<10	18	<10	3	51
10	X05597	5.4	0.85	25	45	<5	1.07	2	17	145	2582	4.84	<10	0.61	843	28	<0.01	9	810	34	10	<20	112	0.01	<10	17	<10	2	38
11	X05598	4.2	1.23	35	55	<5	1.16	2	17	81	2019	4.55	<10	0.89	1271	28	<0.01	7	1290	36	25	<20	109	0.02	<10	21	<10	4	56
12	X05599	5.5	0.82	40	55	<5	0.27	3	17	127	3278	6.78	<10	0.29	289	23	<0.01	8	940	46	10	<20	29	0.02	<10	17	<10	1	58
13	X05600	3.8	0.92	20	45	<5	0.47	1	13	98	2280	4.55	<10	0.50	675	23	<0.01	5	1010	38	5	<20	32	0.01	<10	19	<10	1	63
14	X05601	3.3	1.36	20	55	<5	0.81	1	15	96	1822	5.13	<10	1.05	948	20	<0.01	6	1230	48	10	<20	107	0.02	<10	28	<10	3	81
15	X05602	3.7	1.12	15	45	<5	0.59	1	16	141	2636	5.70	<10	0.78	812	20	<0.01	6	820	44	<5	<20	60	0.02	<10	27	<10	<1	66
16	X05603	3.1	1.82	10	60	<5	1.15	2	13	98	1816	5.25	<10	1.30	1104	22	<0.01	6	1230	50	15	<20	157	0.02	<10	39	<10	3	116
17	X05604	3.1	1.55	15	65	<5	1.18	2	15	120	2303	4.71	<10	1.06	901	33	<0.01	6	1010	44	15	<20	177	0.02	<10	37	<10	2	68
18	X05605	4.1	1.43	<5	60	<5	1.89	2	19	128	2583	5.38	<10	0.95	1082	21	<0.01	7	980	48	10	<20	296	0.02	<10	37	<10	2	67
19	X05606	3.1	1.15	<5	105	<5	2.41	2	12	94	2060	4.52	<10	0.71	1098	32	<0.01	6	1200	38	15	<20	344	0.02	<10	34	<10	4	68
20	X05607	2.8	1.05	<5	80	<5	2.79	2	13	80	1516	4.19	<10	0.62	1350	23	<0.01	5	1290	40	5	<20	342	0.02	<10	29	<10	3	73
21	X05608	2.6	1.37	<5	80	<5	1.86	2	14	80	1428	5.37	<10	1.20	1326	29	0.01	6	1310	48	15	<20	218	0.02	<10	44	<10	4	86
22	X05609	2.3	1.37	10	95	<5	1.49	3	13	104	1526	5.17	<10	1.17	1221	29	0.01	9	1210	46	30	<20	180	0.02	<10	41	<10	4	73
23	X05610	3.1	1.55	5	55	<5	1.41	3	12	92	2349	4.55	<10	1.39	1146	36	<0.01	9	1160	44	35	<20	143	<0.01	<10	37	<10	4	64
24	X05611	<0.2	0.04	30	<5	<5	>10	<1	2	2	6	0.04	<10	1.75	41	<1	<0.01	<1	50	8	15	<20	6106	<0.01	<10	4	<10	<1	<1
25	X05612	3.3	1.17	5	45	<5	0.91	2	18	156	2261	4.66	<10	0.86	868	34	<0.01	7	760	40	20	<20	92	0.01	<10	28	<10	2	43

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05613	3.0	1.47	5	55	<5	1.00	2	14	126	2203	4.88	<10	1.16	1086	32	<0.01	7	980	44	15	<20	101	0.02	<10	31	<10	3	61
27	X05614	2.4	1.88	5	85	<5	1.48	2	16	137	1780	5.47	<10	1.45	1335	31	<0.01	7	1170	50	20	<20	160	0.02	<10	44	<10	4	71
28	X05615	2.9	1.63	<5	65	<5	0.77	1	15	114	2196	5.16	<10	1.04	803	27	<0.01	6	1200	46	10	<20	74	0.02	<10	31	<10	2	78
29	X05616	3.8	1.03	20	50	<5	0.75	2	17	121	2175	6.25	<10	0.55	690	25	<0.01	8	1160	40	10	<20	64	0.02	<10	20	<10	2	48
30	X05617	4.6	0.49	30	50	<5	0.27	2	16	102	2533	6.51	<10	0.10	138	21	<0.01	7	940	42	<5	<20	25	0.02	<10	13	<10	<1	20
31	X05618	3.5	0.60	30	50	<5	0.45	1	19	167	2024	5.67	<10	0.21	360	24	<0.01	8	1030	42	<5	<20	31	0.02	<10	15	<10	2	28
32	X05619	4.6	1.07	10	50	<5	0.58	2	17	118	3170	5.91	<10	0.57	596	34	<0.01	8	910	38	15	<20	43	0.01	<10	22	<10	2	50
33	X05620	3.3	1.16	10	50	<5	1.02	2	13	185	2688	4.28	<10	0.86	899	35	<0.01	10	850	36	25	<20	104	<0.01	<10	26	<10	3	48
34	X05621	2.3	1.14	10	45	<5	1.34	1	14	93	1867	5.66	<10	0.85	1105	19	<0.01	6	1220	48	10	<20	105	0.02	<10	25	<10	3	54
35	X05622	2.6	1.53	5	60	<5	1.32	2	11	113	1880	4.75	<10	1.14	1285	21	<0.01	6	1180	42	20	<20	100	0.02	<10	28	<10	4	71
QC DATA:																													
Repeat:																													
1	X05588	6.4	0.78	110	45	<5	0.44	3	15	111	3191	6.41	<10	0.24	293	23	<0.01	7	840	44	5	<20	36	0.01	<10	19	<10	<1	35
10	X05597	5.3	0.88	25	50	<5	1.09	2	18	149	2585	4.91	<10	0.61	859	30	<0.01	8	870	38	5	<20	118	0.02	<10	17	<10	3	39
19	X05606	3.4	1.18	5	110	<5	2.42	2	12	95	2080	4.54	<10	0.72	1102	31	<0.01	6	1180	40	10	<20	345	0.02	<10	35	<10	3	70
Resplit:																													
1	X05588	6.5	0.80	120	55	<5	0.44	5	16	107	3132	6.67	<10	0.25	312	22	<0.01	7	920	46	5	<20	37	0.01	<10	19	<10	1	38
Standard:																													
PB113A		11.9	0.25	45	70	<5	1.69	31	3	6	2209	1.04	<10	0.13	1555	70	0.02	3	100	5620	20	<20	81	<0.01	<10	10	<10	<1	7111

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5696S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5703

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07205
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X14141	<0.03	<0.001
2	X14142	0.07	0.002
3	X14143	0.37	0.011
4	X14144	0.51	0.015
5	X14145	0.49	0.014
6	X14146	0.81	0.024
7	X14147	0.61	0.018
8	X14148	0.56	0.016
9	X14149	0.40	0.012
10	X14150	0.31	0.009
11	X14151	0.41	0.012
12	X14152	0.31	0.009
13	X14153	0.60	0.017
14	X14154	0.86	0.025
15	X14155	0.65	0.019
16	X14156	0.64	0.019
17	X14157	0.68	0.020
18	X14158	0.56	0.016
19	X14159	1.36	0.040
20	X14160	0.78	0.023
21	X14161	0.45	0.013
22	X14162	0.39	0.011
23	X14163	0.35	0.010
24	X14164	0.43	0.013
25	X14165	<0.03	<0.001
26	X14166	0.34	0.010
27	X14167	0.31	0.009
28	X14168	0.48	0.014
29	X14169	0.43	0.013

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5703 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X14170	0.27	0.008
31	X14171	0.45	0.013
32	X14172	0.34	0.010
33	X14173	0.33	0.010
34	X14174	0.55	0.016
35	X14175	0.47	0.014

QC DATA:

Repeat:

1	X14141	<0.03	<0.001
10	X14150	0.36	0.010
14	X14154	0.92	0.027
19	X14159	1.28	0.037
20	X14160	0.70	0.020

Resplits:

1	X14141	<0.03	<0.001

Standard:

OXK48		3.56	0.104

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5703

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07205
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X14141	<0.2	5.43	85	55	<5	0.25	2	25	46	10	7.73	<10	4.26	1617	<1	0.02	<1	1210	22	<5	<20	10	<0.01	<10	207	<10	6	203
2	X14142	0.3	4.35	50	65	<5	0.24	2	21	57	151	6.89	<10	3.56	1528	14	0.02	2	1320	18	<5	<20	12	<0.01	<10	153	<10	3	282
3	X14143	1.4	1.61	60	40	<5	0.32	2	13	108	689	4.40	<10	1.07	448	66	0.03	12	1530	30	<5	<20	31	<0.01	<10	36	<10	4	136
4	X14144	2.5	0.76	115	30	<5	0.12	4	10	143	1283	3.85	<10	0.41	177	66	0.03	11	540	82	10	<20	27	<0.01	<10	11	<10	<1	141
5	X14145	1.2	1.18	30	40	<5	0.13	2	10	163	1423	4.32	<10	0.77	322	50	0.03	9	520	50	<5	<20	18	<0.01	<10	17	<10	1	130
6	X14146	0.7	1.39	35	45	<5	0.26	1	11	150	1221	4.18	<10	0.82	326	65	0.04	16	1020	28	<5	<20	25	<0.01	<10	22	<10	2	102
7	X14147	1.0	1.73	85	40	<5	0.22	2	17	144	1277	4.90	<10	1.14	388	82	0.04	17	1000	24	<5	<20	22	<0.01	<10	28	<10	3	121
8	X14148	0.6	1.40	25	40	<5	0.19	1	11	124	1010	4.46	<10	0.92	348	337	0.03	11	730	18	<5	<20	22	<0.01	<10	23	<10	2	80
9	X14149	0.7	1.28	45	40	<5	0.24	1	10	123	899	4.00	<10	0.82	312	77	0.04	14	1070	36	<5	<20	20	<0.01	<10	23	<10	2	78
10	X14150	0.6	1.16	25	40	<5	0.19	1	11	121	732	4.00	<10	0.69	288	43	0.03	10	870	34	<5	<20	17	<0.01	<10	17	<10	1	63
11	X14151	1.0	1.41	25	45	<5	0.19	1	12	198	1234	4.38	<10	0.80	276	74	0.03	14	870	34	<5	<20	20	<0.01	<10	23	<10	1	64
12	X14152	0.6	0.97	25	45	<5	0.15	1	10	174	947	3.66	<10	0.49	180	99	0.03	11	670	30	<5	<20	18	<0.01	<10	15	<10	1	44
13	X14153	1.2	1.29	30	45	<5	0.36	1	12	103	903	4.37	<10	0.79	306	55	0.03	15	1640	22	<5	<20	25	<0.01	<10	29	<10	3	72
14	X14154	2.0	0.97	25	40	<5	0.27	3	26	110	1983	6.87	<10	0.54	252	60	0.03	5	1310	58	<5	<20	20	<0.01	<10	16	<10	2	69
15	X14155	1.3	1.02	20	35	<5	0.50	2	13	126	1526	4.58	<10	0.67	440	93	0.03	4	1390	30	<5	<20	20	<0.01	<10	18	<10	2	58
16	X14156	1.5	1.06	15	70	<5	0.55	2	12	140	1230	4.91	<10	0.61	416	80	0.03	3	1450	40	<5	<20	25	<0.01	<10	17	<10	2	47
17	X14157	1.8	1.01	20	40	<5	0.62	2	17	125	1877	6.91	<10	0.68	512	72	0.03	3	1260	32	<5	<20	20	<0.01	<10	16	<10	2	55
18	X14158	1.2	0.94	15	40	<5	0.72	2	16	122	1339	5.67	<10	0.67	627	60	0.02	3	1070	34	<5	<20	18	<0.01	<10	15	<10	2	37
19	X14159	7.4	0.94	205	40	<5	0.55	7	16	179	1825	5.18	<10	0.58	420	57	0.03	4	1340	36	30	<20	22	<0.01	<10	17	<10	2	104
20	X14160	2.3	1.22	45	40	<5	0.63	3	15	139	1178	5.87	<10	0.90	551	36	0.03	3	1390	30	10	<20	20	<0.01	<10	26	<10	3	85
21	X14161	1.7	1.15	15	35	<5	0.77	2	12	126	1429	5.02	<10	0.84	603	56	0.02	3	1380	24	<5	<20	27	<0.01	<10	19	<10	2	68
22	X14162	1.5	1.50	30	35	<5	0.46	2	16	95	988	5.03	<10	1.17	557	101	0.03	2	1650	16	<5	<20	22	<0.01	<10	29	<10	4	101
23	X14163	1.0	1.45	20	40	<5	0.44	2	12	113	964	4.69	<10	1.08	527	191	0.03	2	1500	22	<5	<20	18	<0.01	<10	29	<10	3	95
24	X14164	1.0	1.44	25	40	<5	0.44	2	15	95	805	4.77	<10	1.13	490	146	0.03	2	1530	46	<5	<20	16	<0.01	<10	27	<10	3	137
25	X14165	<0.2	0.01	<5	<5	<5	>10	<1	<1	2	<1	0.01	<10	1.38	24	<1	<0.01	<1	40	<2	<5	<20	4757	<0.01	<10	2	<10	<1	<1

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X14166	1.0	1.09	15	35	<5	0.48	2	18	110	863	5.21	<10	0.77	335	56	0.03	2	1580	74	<5	<20	19	<0.01	<10	18	<10	3	60
27	X14167	0.6	1.40	20	40	<5	0.47	7	13	119	718	4.28	<10	1.12	408	80	0.03	3	1420	60	<5	<20	14	<0.01	<10	24	<10	3	121
28	X14168	0.8	1.17	20	35	<5	0.45	2	12	134	794	4.31	<10	0.76	248	153	0.03	3	1600	46	<5	<20	16	<0.01	<10	19	<10	3	80
29	X14169	0.6	1.52	20	35	<5	0.52	1	12	140	919	4.41	<10	1.17	366	109	0.03	3	1440	38	<5	<20	16	<0.01	<10	29	<10	3	69
30	X14170	3.0	1.24	30	60	<5	1.01	3	19	57	2575	3.55	20	0.60	202	198	0.03	12	610	44	10	<20	64	0.05	<10	39	<10	8	276
31	X14171	0.4	1.48	20	40	<5	0.40	1	17	108	827	5.26	<10	1.14	295	82	0.03	3	1680	20	<5	<20	15	<0.01	<10	27	<10	3	42
32	X14172	<0.2	1.62	20	40	<5	0.43	1	12	93	740	4.12	<10	1.33	348	171	0.03	3	1640	30	<5	<20	14	<0.01	<10	29	<10	4	73
33	X14173	0.5	1.26	20	35	<5	0.41	1	14	96	649	4.43	<10	0.90	246	55	0.03	3	1760	14	<5	<20	13	<0.01	<10	20	<10	3	50
34	X14174	0.7	1.36	20	40	<5	0.34	2	19	109	1013	6.01	<10	1.02	284	83	0.03	2	1590	22	<5	<20	16	<0.01	<10	23	<10	3	63
35	X14175	0.6	1.21	15	35	<5	0.38	2	15	105	605	4.95	<10	0.91	259	131	0.03	2	1710	30	<5	<20	17	<0.01	<10	19	<10	3	37
QC DATA:																													
Repeat:																													
1	X14141	<0.2	5.50	85	55	<5	0.27	2	26	46	10	7.68	<10	4.17	1650	<1	0.02	<1	1240	24	<5	<20	11	<0.01	<10	202	<10	6	207
10	X14150	0.7	1.08	20	40	<5	0.19	1	11	114	725	3.99	<10	0.66	282	43	0.03	10	850	34	<5	<20	16	<0.01	<10	15	<10	1	63
19	X14159	7.2	0.86	200	30	<5	0.53	7	16	168	1809	5.21	<10	0.57	418	48	0.03	4	1320	36	25	<20	22	<0.01	<10	16	<10	2	105
Resplit:																													
1	X14141	0.2	5.51	130	60	<5	0.26	2	34	49	8	7.91	<10	4.19	1697	<1	0.02	<1	1240	22	<5	<20	10	<0.01	<10	204	<10	5	215
Standard:																													
PB113A		11.0	0.27	50	65	<5	1.79	37	2	<1	2284	1.04	<10	0.10	1491	61	0.02	1	100	5726	5	<20	105	0.01	<10	7	<10	1	6972

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/n5703S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5704

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07190
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X12211	0.90	0.026
2	X12212	0.89	0.026
3	X12213	0.71	0.021
4	X12214	0.96	0.028
5	X12215	0.63	0.018
6	X12216	0.54	0.016
7	X12217	1.22	0.036
8	X12218	0.95	0.028
9	X12219	0.61	0.018
10	X12220	0.76	0.022
11	X12221	0.81	0.024
12	X12222	0.60	0.017
13	X12223	0.75	0.022
14	X12224	1.86	0.054
15	X12225	1.19	0.035
16	X12226	1.01	0.029
17	X12227	1.06	0.031
18	X12228	0.48	0.014
19	X12229	0.70	0.020
20	X12230	0.62	0.018
21	X12231	0.61	0.018
22	X12232	0.58	0.017
23	X12233	0.51	0.015
24	X12234	0.32	0.009
25	X12235	0.54	0.016
26	X12236	0.48	0.014
27	X12237	0.30	0.009
28	X12238	0.33	0.010

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5704 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	X12239	1.56	0.045
30	X12240	0.34	0.010
31	X12241	<0.03	<0.001
32	X12242	0.37	0.011
33	X12243	0.54	0.016
34	X12244	0.40	0.012
35	X12245	0.26	0.008

QC DATA:

Repeat:

1	X12211	1.02	0.030
7	X12217	1.27	0.037
10	X12220	0.84	0.024
14	X12224	1.70	0.050
19	X12229	0.70	0.020
29	X12239	1.50	0.044

Resplits:

1	X12211	0.89	0.026

Standard:

OXK48		3.57	0.104

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 2007-5704

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07190
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X12211	2.4	1.13	50	45	<5	1.93	2	8	131	1052	4.85	<10	0.73	997	12	0.02	2	780	18	<5	<20	106	<0.01	<10	48	<10	3	77
2	X12212	2.4	0.84	100	40	<5	2.70	2	9	121	900	4.50	<10	0.59	1207	11	0.02	1	800	16	5	<20	140	<0.01	<10	38	<10	4	58
3	X12213	1.9	0.79	25	55	<5	1.31	2	7	108	1245	4.84	<10	0.55	746	11	0.02	1	720	12	<5	<20	109	<0.01	<10	66	<10	3	61
4	X12214	2.9	0.97	35	45	<5	1.23	2	10	137	1850	4.53	<10	0.72	872	10	0.02	2	580	14	<5	<20	111	<0.01	<10	52	<10	3	59
5	X12215	2.8	0.78	20	55	<5	1.06	2	10	144	1887	4.99	<10	0.56	867	14	0.02	2	600	16	<5	<20	92	<0.01	<10	59	<10	3	69
6	X12216	2.1	1.17	20	125	<5	0.91	2	8	134	1543	6.32	<10	0.92	900	10	0.02	2	1020	16	<5	<20	77	<0.01	<10	94	<10	3	87
7	X12217	4.2	0.88	25	50	<5	0.97	3	11	127	3168	6.96	<10	0.81	874	17	0.02	<1	570	22	<5	<20	80	<0.01	<10	128	<10	3	60
8	X12218	2.4	1.07	45	55	<5	1.18	2	10	146	1847	6.25	<10	0.93	1159	8	0.02	1	790	18	<5	<20	89	<0.01	<10	88	<10	3	80
9	X12219	2.1	0.98	25	85	<5	0.99	2	10	105	1481	5.37	<10	0.77	990	11	0.02	<1	830	24	<5	<20	87	<0.01	<10	61	<10	3	96
10	X12220	3.2	0.79	50	40	<5	1.30	2	8	137	1436	5.28	<10	0.72	1305	8	0.02	1	640	16	<5	<20	83	<0.01	<10	50	<10	2	77
11	X12221	6.0	0.70	80	40	<5	1.00	2	10	162	1356	5.51	<10	0.63	1088	11	0.02	2	580	14	<5	<20	70	<0.01	<10	54	<10	2	65
12	X12222	2.9	0.99	60	50	<5	1.52	2	10	101	1145	5.21	<10	0.81	915	11	0.02	1	1090	16	<5	<20	126	<0.01	<10	57	<10	4	79
13	X12223	3.0	1.04	110	40	<5	2.41	2	10	114	843	4.50	<10	0.78	1222	11	0.02	2	980	20	5	<20	167	<0.01	<10	30	<10	4	63
14	X12224	5.9	0.84	90	40	<5	4.17	2	13	101	851	5.57	<10	2.28	3123	22	0.02	<1	540	20	10	<20	127	<0.01	<10	31	<10	5	44
15	X12225	3.3	0.66	85	40	<5	2.79	2	9	150	780	4.65	<10	1.18	1901	8	0.02	3	730	18	10	<20	127	<0.01	<10	23	<10	5	31
16	X12226	3.7	1.18	65	65	10	0.76	4	15	58	3256	3.87	20	0.50	286	197	0.03	16	410	132	30	<20	44	0.03	<10	37	<10	8	162
17	X12227	2.4	0.92	80	40	<5	0.61	2	8	146	1124	4.95	<10	0.73	457	10	0.02	2	740	14	<5	<20	67	<0.01	<10	35	<10	2	62
18	X12228	1.5	1.51	70	50	<5	0.97	2	9	175	766	5.57	<10	1.14	835	9	0.02	3	850	10	<5	<20	87	<0.01	<10	58	<10	2	96
19	X12229	2.0	1.35	40	40	<5	1.16	1	8	91	1035	4.57	<10	1.13	835	11	0.02	1	1010	10	<5	<20	92	<0.01	<10	37	<10	3	92
20	X12230	1.8	1.11	125	45	<5	2.46	2	8	145	853	5.06	<10	0.75	1423	8	0.02	3	1000	14	<5	<20	142	<0.01	<10	33	<10	4	62
21	X12231	1.8	0.82	80	35	<5	3.18	2	10	105	792	5.21	<10	0.76	1862	13	0.02	1	750	16	<5	<20	160	<0.01	<10	35	<10	5	45
22	X12232	2.3	0.88	35	35	<5	1.61	2	9	181	1347	4.93	<10	0.84	970	5	0.02	2	510	14	<5	<20	102	<0.01	<10	44	<10	2	55
23	X12233	1.5	1.31	55	40	<5	1.24	2	8	109	624	5.16	<10	1.17	902	9	0.02	1	690	12	<5	<20	86	<0.01	<10	57	<10	3	77
24	X12234	1.6	1.35	60	55	<5	1.34	1	9	105	975	4.53	<10	1.23	1088	6	0.02	2	1100	10	<5	<20	77	<0.01	<10	32	<10	4	75
25	X12235	1.6	1.34	50	45	<5	1.01	2	8	113	980	6.12	<10	1.15	927	7	0.02	<1	740	10	<5	<20	84	<0.01	<10	94	<10	3	77

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X12236	1.9	1.11	55	45	<5	0.92	2	10	145	1188	5.50	<10	0.95	838	7	0.02	2	610	12	<5	<20	77	<0.01	<10	76	<10	3	78
27	X12237	1.4	0.84	45	40	<5	1.67	1	6	107	787	3.32	<10	1.09	1276	9	0.02	2	660	10	<5	<20	125	<0.01	<10	39	<10	4	53
28	X12238	1.0	0.80	25	45	<5	2.20	1	8	137	592	3.82	<10	0.95	1402	8	0.02	3	450	8	<5	<20	124	<0.01	<10	46	<10	4	50
29	X12239	1.3	1.00	35	45	<5	2.12	2	8	83	571	4.04	<10	1.18	1571	7	0.02	1	900	16	<5	<20	121	<0.01	<10	47	<10	4	66
30	X12240	1.5	0.67	10	50	<5	1.86	1	7	135	1091	3.46	<10	0.70	1219	5	0.02	3	540	14	<5	<20	122	<0.01	<10	53	<10	5	48
31	X12241	<0.2	1.04	10	260	<5	0.71	<1	7	99	3	2.26	<10	0.62	563	<1	0.09	7	940	10	<5	<20	89	0.14	<10	42	<10	5	45
32	X12242	1.2	0.69	30	45	<5	1.09	2	8	134	754	4.41	<10	0.54	743	8	0.02	2	510	12	<5	<20	80	<0.01	<10	70	<10	2	70
33	X12243	1.6	1.11	50	65	<5	1.22	2	9	124	1069	5.20	<10	0.88	1053	8	0.02	2	940	14	<5	<20	64	<0.01	<10	79	<10	4	107
34	X12244	1.8	0.60	15	165	<5	2.36	2	12	124	1361	5.07	<10	0.51	1408	8	0.02	1	480	12	<5	<20	151	<0.01	<10	123	<10	4	64
35	X12245	1.0	0.81	10	335	<5	2.28	2	9	115	848	5.31	<10	0.72	1300	8	0.03	2	920	22	<5	<20	152	0.01	<10	154	<10	5	81
QC DATA:																													
Repeat:																													
1	X12211	2.3	1.13	50	45	<5	1.92	2	8	131	1023	4.92	<10	0.74	974	11	0.02	2	760	14	<5	<20	108	<0.01	<10	51	<10	3	72
10	X12220	3.3	0.84	55	50	<5	1.36	2	8	146	1479	5.50	<10	0.73	1379	9	0.02	1	670	16	<5	<20	88	<0.01	<10	53	<10	3	82
19	X12229	2.3	1.32	40	45	<5	1.11	1	7	90	995	4.58	<10	1.16	794	11	0.02	1	950	6	<5	<20	93	<0.01	<10	41	<10	3	85
Resplit:																													
1	X12211	2.4	1.18	55	50	<5	1.85	2	8	139	1013	5.07	<10	0.76	971	12	0.02	2	810	16	<5	<20	107	<0.01	<10	54	<10	3	75
Standard:																													
PB113A		11.0	0.28	45	70	<5	1.75	38	2	<1	2235	1.03	<10	0.10	1468	69	0.02	1	100	5434	5	<20	86	0.01	<10	8	<10	1	6982

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5703
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5705

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07194
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	XO5553	0.19	0.006
2	XO5554	0.17	0.005
3	XO5555	0.19	0.006
4	XO5556	0.32	0.009
5	XO5557	0.22	0.006
6	XO5558	0.32	0.009
7	XO5559	0.33	0.010
8	XO5560	0.33	0.010
9	XO5561	0.34	0.010
10	XO5562	0.28	0.008
11	XO5563	0.21	0.006
12	XO5564	0.21	0.006
13	XO5565	0.28	0.008
14	XO5566	0.26	0.008
15	XO5567	0.34	0.010
16	XO5568	0.25	0.007
17	XO5569	0.24	0.007
18	XO5570	0.18	0.005
19	XO5571	0.17	0.005
20	XO5572	0.24	0.007
21	XO5573	0.31	0.009
22	XO5574	0.71	0.021
23	XO5575	0.61	0.018
24	XO5576	0.70	0.020
25	XO5577	0.74	0.022
26	XO5578	0.99	0.029
27	XO5579	<0.03	<0.001
28	XO5580	0.99	0.029
29	XO5581	0.97	0.028

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5705 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	XO5582	0.84	0.024
31	XO5583	0.97	0.028
32	XO5584	0.97	0.028
33	XO5585	1.08	0.031
34	XO5586	0.93	0.027
35	XO5587	1.25	0.036

QC DATA:

Repeat:

1	XO5553	0.17	0.005
10	XO5562	0.27	0.008
19	XO5571	0.21	0.006

Resplits:

1	XO5553	0.17	0.005

Standard:

OXK48		3.53	0.103

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5705

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07194
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	XO5553	0.2	1.21	10	35	<5	1.96	1	9	92	478	3.38	<10	0.88	281	46	0.03	2	1560	10	<5	<20	104	<0.01	<10	30	<10	5	30
2	XO5554	0.3	1.31	10	40	<5	1.85	1	10	90	493	3.83	<10	1.12	360	23	0.03	2	1550	14	<5	<20	82	<0.01	<10	33	<10	6	39
3	XO5555	0.4	1.24	10	35	<5	1.40	1	12	86	616	4.51	<10	1.00	372	40	0.03	1	1530	12	<5	<20	34	<0.01	<10	23	<10	5	33
4	XO5556	0.9	0.81	10	35	<5	1.07	2	14	85	978	3.99	<10	0.62	228	28	0.03	2	1370	18	<5	<20	28	<0.01	<10	12	<10	3	20
5	XO5557	0.4	1.29	10	40	<5	0.79	2	10	66	664	3.55	<10	1.03	249	20	0.03	1	1590	12	<5	<20	27	<0.01	<10	24	<10	5	48
6	XO5558	0.5	1.03	10	40	<5	1.26	2	12	89	714	4.57	<10	0.84	252	98	0.03	2	1330	14	<5	<20	47	<0.01	<10	26	<10	5	26
7	XO5559	0.3	0.97	10	40	<5	1.85	2	12	93	692	4.09	<10	0.71	292	60	0.04	2	1310	10	<5	<20	63	<0.01	<10	26	<10	5	18
8	XO5560	0.2	1.05	15	45	<5	1.80	2	13	110	714	4.28	<10	0.75	299	53	0.04	3	1380	14	<5	<20	59	<0.01	<10	31	<10	5	23
9	XO5561	0.7	1.07	15	45	<5	1.50	2	17	97	759	4.91	<10	0.79	344	146	0.03	3	1420	28	<5	<20	49	<0.01	<10	24	<10	5	64
10	XO5562	0.6	1.04	15	40	<5	1.26	4	14	78	738	4.66	<10	0.79	294	50	0.03	2	1470	50	<5	<20	49	<0.01	<10	20	<10	4	59
11	XO5563	<0.2	1.26	15	40	<5	1.42	2	9	81	454	4.15	<10	1.02	336	37	0.04	2	1600	20	<5	<20	59	<0.01	<10	40	<10	5	39
12	XO5564	0.3	1.11	15	45	<5	2.84	2	12	131	532	4.49	<10	0.89	513	79	0.04	4	1340	18	<5	<20	71	<0.01	<10	33	<10	6	26
13	XO5565	0.4	1.31	15	45	<5	3.00	2	13	115	539	4.47	<10	1.04	639	29	0.04	3	1470	12	<5	<20	68	<0.01	<10	37	<10	5	38
14	XO5566	0.5	1.34	15	45	<5	1.29	2	11	93	625	4.19	<10	1.05	383	58	0.03	3	1550	8	<5	<20	46	<0.01	<10	33	<10	5	46
15	XO5567	0.8	1.07	15	45	<5	1.48	16	16	102	856	5.15	<10	0.79	365	69	0.03	2	1550	36	<5	<20	47	<0.01	<10	19	<10	4	159
16	XO5568	0.5	1.32	15	50	<5	2.21	2	16	85	589	4.93	<10	1.09	558	41	0.03	3	1570	10	<5	<20	46	<0.01	<10	33	<10	6	45
17	XO5569	0.3	0.82	10	45	<5	2.44	3	17	126	487	5.58	<10	0.54	503	56	0.02	3	1530	20	<5	<20	63	<0.01	<10	15	<10	5	26
18	XO5570	0.4	1.23	15	50	<5	2.24	2	13	97	542	4.13	<10	1.00	504	131	0.03	3	1630	20	<5	<20	47	<0.01	<10	30	<10	6	45
19	XO5571	0.4	1.02	15	40	<5	1.53	3	14	94	389	5.01	<10	0.81	370	90	0.02	2	1520	20	<5	<20	33	<0.01	<10	23	<10	5	38
20	XO5572	0.6	1.45	20	45	<5	2.70	4	23	91	557	6.60	<10	1.26	730	73	0.02	3	1610	14	<5	<20	50	<0.01	<10	36	<10	6	70
21	XO5573	0.4	1.07	15	40	<5	1.77	2	15	91	596	4.53	<10	0.78	441	57	0.02	3	1660	14	<5	<20	50	<0.01	<10	17	<10	5	42
22	XO5574	2.8	0.86	20	60	<5	1.81	3	12	164	1996	5.75	<10	0.69	699	15	0.04	3	1130	16	<5	<20	142	<0.01	<10	68	<10	4	91
23	XO5575	2.4	1.03	25	55	<5	1.30	3	11	149	1598	5.10	<10	0.68	721	20	0.02	3	1250	16	<5	<20	86	<0.01	<10	34	<10	4	90
24	XO5576	2.4	0.99	30	50	<5	1.12	3	11	153	1724	5.45	<10	0.63	625	20	0.02	3	1330	18	<5	<20	79	<0.01	<10	30	<10	4	69
25	XO5577	2.5	1.09	25	60	<5	1.64	3	10	133	1685	4.50	<10	0.70	857	19	0.01	3	1250	16	<5	<20	143	<0.01	<10	24	<10	4	68

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	XO5578	3.8	0.78	25	55	<5	1.30	2	11	157	2673	4.12	<10	0.40	622	18	0.01	3	1000	20	<5	<20	119	<0.01	<10	17	<10	4	46
27	XO5579	<0.2	0.12	<5	<5	<5	>10	<1	<1	3	4	0.15	<10	1.25	34	<1	0.02	<1	70	<2	<5	<20	6129	0.01	<10	1	<10	<1	2
28	XO5580	3.7	1.15	70	85	10	0.85	5	16	64	3252	4.33	20	0.45	313	223	0.03	18	440	118	30	<20	41	0.04	<10	38	<10	8	184
29	XO5581	3.5	1.19	25	55	<5	1.07	3	10	163	2334	6.04	<10	0.74	586	15	0.02	3	1110	16	<5	<20	88	<0.01	<10	29	<10	4	70
30	XO5582	3.3	0.74	40	45	<5	1.91	3	12	213	2352	4.57	<10	0.36	806	22	0.01	4	910	18	<5	<20	166	<0.01	<10	15	<10	3	42
31	XO5583	3.4	0.94	30	70	<5	2.03	2	11	157	2069	4.38	<10	0.39	949	25	0.01	4	1150	18	<5	<20	189	<0.01	<10	15	<10	4	60
32	XO5584	3.6	1.08	55	70	<5	1.88	2	11	160	1796	4.72	<10	0.42	949	22	0.01	3	1290	18	<5	<20	186	<0.01	<10	16	<10	4	72
33	XO5585	6.1	0.38	130	35	<5	0.73	2	9	253	2689	4.49	<10	0.07	424	22	0.01	5	730	34	5	<20	68	<0.01	<10	7	<10	2	37
34	XO5586	2.9	1.00	50	65	<5	1.60	2	10	146	1783	4.46	<10	0.46	1004	20	0.01	3	1010	12	<5	<20	177	<0.01	<10	15	<10	4	63
35	XO5587	4.4	1.21	20	70	<5	1.67	2	11	166	3304	4.62	<10	0.67	1176	17	0.01	4	1100	12	<5	<20	181	<0.01	<10	19	<10	4	61
QC DATA:																													
Repeat:																													
1	XO5553	0.3	1.33	15	45	<5	2.08	2	11	107	518	4.08	<10	1.00	325	55	0.04	3	1570	8	<5	<20	115	<0.01	<10	34	<10	6	28
10	XO5562	0.6	1.10	15	45	<5	1.37	4	15	85	758	4.85	<10	0.78	320	50	0.03	2	1550	52	<5	<20	54	<0.01	<10	21	<10	4	63
19	XO5571	0.6	1.05	15	45	<5	1.71	2	15	100	381	5.18	<10	0.80	389	96	0.02	3	1540	20	<5	<20	42	<0.01	<10	24	<10	5	41
Resplit:																													
1	XO5553	0.2	1.32	15	40	<5	2.05	2	11	86	520	4.32	<10	1.00	335	45	0.02	2	1580	8	<5	<20	114	<0.01	<10	33	<10	6	34
Standard:																													
PB113A		11.0	0.29	50	60	<5	1.76	38	2	<1	2232	1.20	<10	0.10	1526	67	0.01	1	90	5552	5	<20	86	0.01	<10	5	<10	1	7142

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5703
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5706

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07185
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10287	0.63	0.018
2	X10288	0.50	0.015
3	X10289	0.57	0.017
4	X10290	0.99	0.029
5	X10291	0.71	0.021
6	X10292	0.63	0.018
7	X10293	0.99	0.029
8	X10294	<0.03	<0.001
9	X10295	0.83	0.024
10	X10296	0.80	0.023
11	X10297	0.78	0.023
12	X10298	0.73	0.021
13	X10299	1.40	0.041
14	X10300	1.00	0.029
15	X10301	0.74	0.022
16	X10302	0.61	0.018
17	X10303	0.57	0.017
18	X10304	0.86	0.025
19	X10305	0.64	0.019
20	X10306	4.95	0.144
21	X10307	0.83	0.024
22	X10308	0.62	0.018
23	X10309	1.06	0.031
24	X10310	1.01	0.029
25	X10311	0.82	0.024
26	X10312	0.47	0.014
27	X10313	0.36	0.010
28	X10314	0.72	0.021
29	X10315	0.68	0.020

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5706 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X10316	0.77	0.022
31	X10317	0.83	0.024
32	X10318	0.77	0.022
33	X10319	0.53	0.015
34	X10320	0.61	0.018
35	X10321	0.56	0.016
QC DATA:			
Repeat:			
1	X10287	0.61	0.018
10	X10296	0.81	0.024
13	X10299	1.31	0.038
19	X10305	0.70	0.020
20	X10306	5.10	0.149
Resplits:			
1	X10287	0.71	0.021
Standard:			
OXK48		3.49	0.102

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 2007-5706

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07185
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10287	2.5	1.03	50	45	<5	1.79	3	9	112	1401	6.09	<10	0.77	1181	7	0.02	<1	810	14	<5	<20	73	<0.01	<10	22	<10	3	50
2	X10288	1.8	0.83	20	70	<5	1.63	3	9	100	1335	6.25	<10	0.54	761	91	0.02	<1	900	8	<5	<20	101	<0.01	<10	39	<10	4	50
3	X10289	4.4	0.72	15	55	<5	1.46	3	11	106	3418	6.77	<10	0.50	687	8	0.02	<1	710	12	<5	<20	114	<0.01	<10	40	<10	4	59
4	X10290	3.6	1.18	75	80	10	0.88	5	17	68	3273	4.53	20	0.46	332	225	0.03	18	510	122	30	<20	40	0.04	<10	39	<10	9	171
5	X10291	3.2	0.88	30	50	<5	0.85	3	7	135	2168	7.13	<10	0.64	688	25	0.02	<1	770	14	<5	<20	48	<0.01	<10	44	<10	3	57
6	X10292	2.7	0.74	15	90	<5	1.78	3	7	105	2219	6.16	<10	0.50	637	7	0.02	<1	1030	14	<5	<20	226	<0.01	<10	59	<10	4	42
7	X10293	3.8	0.68	20	55	<5	1.21	3	12	156	3252	5.79	<10	0.41	706	9	0.02	2	970	12	<5	<20	92	<0.01	<10	46	<10	3	40
8	X10294	<0.2	1.03	10	270	<5	0.75	<1	8	100	5	2.49	<10	0.53	580	<1	0.08	7	980	10	<5	<20	92	0.16	<10	41	<10	5	50
9	X10295	3.1	0.69	15	70	<5	0.73	3	7	121	2294	6.03	<10	0.39	471	11	0.02	<1	1090	10	<5	<20	72	<0.01	<10	55	<10	3	55
10	X10296	3.9	0.97	25	60	<5	0.87	3	10	124	2450	7.03	<10	0.64	682	18	0.02	<1	1190	16	<5	<20	93	<0.01	<10	51	<10	4	91
11	X10297	3.3	0.87	35	40	<5	0.75	3	10	102	2066	6.12	<10	0.54	774	38	0.01	<1	990	20	<5	<20	56	<0.01	<10	27	<10	3	79
12	X10298	2.6	1.02	25	55	<5	0.78	3	7	124	1848	6.95	<10	0.68	969	9	0.01	<1	1120	18	<5	<20	53	<0.01	<10	51	<10	4	101
13	X10299	3.3	1.04	25	60	<5	0.81	4	15	98	2688	9.18	<10	0.75	1064	9	0.02	<1	990	18	<5	<20	45	<0.01	<10	88	<10	3	120
14	X10300	4.1	0.74	15	75	<5	0.61	3	9	132	3188	6.52	<10	0.44	610	8	0.02	<1	1020	16	<5	<20	53	<0.01	<10	72	<10	3	70
15	X10301	5.3	0.92	20	60	<5	0.76	3	10	115	2598	6.54	<10	0.65	1024	30	0.01	<1	950	12	<5	<20	49	<0.01	<10	54	<10	4	85
16	X10302	7.7	1.04	35	50	<5	1.40	4	9	118	1727	6.94	<10	0.73	1454	7	0.02	1	1220	18	<5	<20	79	<0.01	<10	34	<10	4	109
17	X10303	9.7	1.00	50	50	<5	1.00	3	7	93	1782	6.62	<10	0.67	977	13	0.01	<1	1130	18	10	<20	71	<0.01	<10	37	<10	3	91
18	X10304	3.7	0.75	20	65	<5	0.86	3	10	166	2885	5.43	<10	0.46	699	10	0.01	2	560	16	<5	<20	63	<0.01	<10	33	<10	2	61
19	X10305	3.0	0.60	30	50	<5	0.87	6	16	114	1849	6.77	<10	0.36	645	14	0.01	<1	620	54	5	<20	53	<0.01	<10	29	<10	2	161
20	X10306	13.9	0.91	85	45	<5	0.91	3	10	142	2300	6.93	<10	0.56	692	8	0.01	<1	730	28	5	<20	50	<0.01	<10	22	<10	2	83
21	X10307	3.9	1.15	30	55	<5	0.79	3	14	122	2233	6.84	<10	0.75	866	10	0.01	<1	870	12	<5	<20	46	<0.01	<10	54	<10	3	109
22	X10308	2.6	0.92	15	65	<5	1.03	4	13	125	2223	7.80	<10	0.60	810	9	0.02	<1	1100	28	<5	<20	80	<0.01	<10	70	<10	4	70
23	X10309	5.1	1.02	50	60	<5	0.54	4	25	121	2015	>10	<10	0.63	712	12	0.02	<1	810	18	<5	<20	33	<0.01	<10	67	<10	2	81
24	X10310	2.8	1.26	40	60	<5	0.80	9	15	147	1639	9.00	<10	0.78	852	9	0.02	<1	1190	24	<5	<20	47	<0.01	<10	70	<10	4	319
25	X10311	3.5	0.74	15	55	<5	0.96	4	12	160	2937	6.32	<10	0.47	635	11	0.01	1	690	22	<5	<20	68	<0.01	<10	59	<10	3	120

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10312	1.9	0.92	15	55	<5	1.32	3	9	147	1431	6.74	<10	0.57	832	7	0.02	1	810	16	<5	<20	77	<0.01	<10	54	<10	4	101
27	X10313	1.1	0.65	15	60	<5	1.14	3	14	129	859	6.57	<10	0.39	548	11	0.01	<1	560	14	<5	<20	54	<0.01	<10	57	<10	2	44
28	X10314	2.4	0.75	15	65	<5	2.58	3	11	126	2195	6.88	<10	0.62	1253	7	0.02	1	1090	38	<5	<20	389	<0.01	<10	76	<10	5	127
29	X10315	6.8	0.90	15	50	<5	0.87	4	13	136	2674	8.04	<10	0.67	985	14	0.02	<1	940	24	<5	<20	41	<0.01	<10	76	<10	3	138
30	X10316	4.3	0.73	15	50	<5	0.95	5	13	157	2881	7.93	<10	0.59	1152	8	0.01	1	900	54	<5	<20	45	<0.01	<10	55	<10	3	154
31	X10317	3.4	0.51	10	45	<5	0.57	3	21	141	3764	7.35	<10	0.30	417	9	0.01	<1	510	22	<5	<20	36	<0.01	<10	53	<10	2	54
32	X10318	2.9	0.73	15	55	<5	1.93	4	15	143	2416	7.24	<10	0.51	869	10	0.02	2	1110	30	<5	<20	201	<0.01	<10	59	<10	4	115
33	X10319	1.5	0.70	15	65	<5	2.49	5	9	109	620	6.00	<10	0.45	835	10	0.02	<1	1050	30	<5	<20	257	<0.01	<10	45	<10	4	200
34	X10320	6.5	0.34	50	45	15	2.06	4	14	213	2366	8.15	<10	0.13	825	13	0.02	2	630	36	5	<20	125	<0.01	<10	20	<10	2	61
35	X10321	2.1	0.51	10	55	<5	2.98	3	12	140	1460	5.82	<10	0.29	802	10	0.02	1	690	12	<5	<20	232	<0.01	<10	36	<10	3	88
QC DATA:																													
Repeat:																													
1	X10287	2.6	1.07	50	45	<5	1.90	3	9	122	1392	6.29	<10	0.77	1262	8	0.01	<1	820	12	<5	<20	79	<0.01	<10	24	<10	3	40
10	X10296	3.9	1.02	30	55	<5	0.88	3	10	126	2480	7.10	<10	0.66	653	18	0.02	<1	1200	12	<5	<20	92	<0.01	<10	52	<10	4	87
19	X10305	3.1	0.60	30	45	<5	0.86	6	16	115	1772	6.67	<10	0.36	633	13	0.01	<1	610	54	<5	<20	53	<0.01	<10	30	<10	2	156
Resplit:																													
1	X10287	2.7	1.09	55	50	<5	1.97	3	11	155	1526	6.50	<10	0.82	1310	7	0.01	1	880	12	<5	<20	83	<0.01	10	26	<10	4	45
Standard:																													
PB113A		11.4	0.25	40	70	<5	1.60	34	2	2	2263	1.14	<10	0.10	1576	71	0.01	1	100	5571	5	<20	90	0.01	<10	6	<10	1	7165

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5703
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5707

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07197
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05658	1.60	0.047
2	X05659	0.87	0.025
3	X05660	0.82	0.024
4	X05661	0.93	0.027
5	X05662	0.66	0.019
6	X05663	1.04	0.030
7	X05664	0.82	0.024
8	X05665	0.68	0.020
9	X05666	0.68	0.020
10	X05667	0.82	0.024
11	X05668	0.62	0.018
12	X05669	0.69	0.020
13	X05670	0.36	0.010
14	X05671	0.53	0.015
15	X05672	0.62	0.018
16	X05673	0.81	0.024
17	X05674	0.44	0.013
18	X05675	1.12	0.033
19	X05676	1.02	0.030
20	X05677	0.33	0.010
21	X05678	<0.03	<0.001
22	X05679	0.19	0.006
23	X05680	0.22	0.006
24	X05681	0.23	0.007
25	X05682	0.44	0.013
26	X05683	0.38	0.011
27	X05684	0.43	0.013
28	X05685	0.64	0.019
29	X05686	0.51	0.015

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5707 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X05687	0.62	0.018
31	X05688	0.26	0.008
32	X05689	0.30	0.009
33	X05690	0.37	0.011
34	X05691	0.45	0.013
35	X05692	0.47	0.014

QC DATA:

Repeat:

6	X05663	1.18	0.034
10	X05667	1.13	0.033
19	X05676	1.06	0.031

Resplits:

2	X05659	0.78	0.023

Standard:

OXK48		3.56	0.104

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5707

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07197
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05658	0.2	0.69	2190	70	10	0.77	27	29	24	58	5.03	10	2.01	757	6	0.15	105	1090	20	30	<20	60	0.07	<10	23	<10	7	61
2	X05659	4.1	0.99	5	70	<5	0.28	2	14	139	2523	5.75	<10	0.50	275	27	<0.01	9	980	38	15	<20	29	0.01	<10	19	<10	3	68
3	X05660	3.7	0.83	<5	50	<5	0.48	1	12	165	2340	4.37	<10	0.43	349	45	<0.01	6	770	58	<5	<20	36	0.01	<10	17	<10	<1	65
4	X05661	4.9	1.41	<5	70	<5	0.27	3	14	115	2702	6.25	<10	0.80	403	31	<0.01	8	840	46	15	<20	30	0.02	<10	26	<10	2	104
5	X05662	3.8	1.02	<5	55	<5	0.24	2	12	176	2114	5.24	<10	0.52	283	20	0.01	8	760	48	5	<20	20	0.02	<10	20	<10	1	82
6	X05663	4.6	1.55	<5	70	<5	0.51	3	13	144	3956	5.75	<10	0.92	556	34	<0.01	8	630	42	15	<20	46	0.01	<10	33	<10	<1	104
7	X05664	3.5	1.34	<5	105	<5	0.57	1	13	174	2392	5.09	<10	0.76	579	18	0.01	7	700	46	10	<20	104	0.03	<10	25	<10	6	88
8	X05665	2.8	1.13	<5	70	<5	0.65	1	10	197	1906	4.37	<10	0.61	600	26	<0.01	8	770	46	10	<20	64	0.01	<10	24	<10	2	64
9	X05666	3.9	0.98	<5	65	<5	0.56	1	12	166	1810	4.61	<10	0.68	656	21	<0.01	7	850	40	<5	<20	45	0.03	<10	16	<10	3	85
10	X05667	3.4	1.00	10	60	<5	0.63	1	13	158	1800	4.32	<10	0.64	482	17	<0.01	6	950	32	<5	<20	54	0.02	<10	18	<10	2	59
11	X05668	2.6	1.43	15	140	<5	0.93	2	9	126	1565	3.76	<10	1.00	741	28	<0.01	8	1310	38	25	<20	86	0.01	<10	25	<10	4	91
12	X05669	2.0	1.14	<5	150	<5	1.96	3	11	152	1684	4.07	<10	0.97	1249	20	<0.01	8	850	40	20	<20	196	0.02	<10	32	<10	2	91
13	X05670	1.7	0.89	<5	60	<5	2.82	4	12	136	1522	2.92	<10	0.77	1325	20	<0.01	4	560	86	5	<20	334	0.02	<10	19	<10	3	99
14	X05671	3.3	1.06	<5	210	<5	2.36	2	12	101	1579	3.85	<10	1.17	931	19	0.04	6	1120	38	15	<20	396	0.02	<10	76	<10	4	88
15	X05672	1.4	1.05	<5	95	<5	2.12	1	14	142	1300	4.04	<10	0.99	868	17	0.02	8	970	34	10	<20	266	0.03	<10	49	<10	5	85
16	X05673	1.8	0.98	<5	90	<5	2.55	3	13	135	1764	3.80	<10	1.11	1202	14	0.01	6	920	42	20	<20	254	0.02	<10	32	<10	8	103
17	X05674	1.4	0.83	<5	80	<5	2.02	2	10	132	1470	3.88	<10	0.94	1170	17	<0.01	7	990	34	20	<20	140	0.02	<10	29	<10	4	73
18	X05675	1.5	0.96	<5	145	<5	2.20	1	10	120	1117	3.47	<10	0.84	976	14	0.02	5	1070	38	<5	<20	206	0.02	<10	32	<10	4	63
19	X05676	1.5	0.83	<5	65	<5	4.54	6	17	115	959	4.53	<10	0.67	1533	17	0.02	7	1060	256	10	<20	309	0.03	<10	43	<10	3	121
20	X05677	1.2	0.99	<5	150	<5	2.52	3	11	113	970	3.74	<10	0.86	1068	20	0.02	11	980	58	40	<20	190	0.01	<10	38	<10	3	93
21	X05678	<0.2	0.02	10	<5	<5	>10	<1	1	3	2	0.02	<10	0.98	23	<1	<0.01	<1	30	6	<5	<20	5020	0.01	<10	2	<10	<1	<1
22	X05679	0.6	0.88	<5	325	<5	1.49	2	7	99	542	3.54	<10	0.60	776	15	0.02	7	1010	46	20	<20	130	0.02	<10	33	<10	4	54
23	X05680	0.7	1.10	<5	200	<5	2.35	1	9	97	687	3.23	<10	1.05	1585	13	0.01	5	1080	38	20	<20	129	0.02	<10	26	<10	5	73
24	X05681	0.8	0.82	<5	195	<5	2.34	1	8	107	766	3.06	<10	0.62	1152	14	0.01	5	1000	26	5	<20	155	0.02	<10	22	<10	4	41
25	X05682	1.7	0.93	5	120	<5	2.56	2	9	85	1525	2.96	<10	0.86	1218	12	<0.01	5	1080	28	15	<20	151	0.02	<10	22	<10	4	50

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05683	1.2	0.83	<5	145	<5	2.36	1	9	133	1089	2.84	<10	0.67	1095	13	<0.01	6	1090	32	5	<20	122	0.02	<10	26	<10	4	61
27	X05684	1.5	0.93	<5	175	<5	2.21	1	8	99	1400	3.21	<10	0.76	1006	12	0.01	3	1270	32	5	<20	106	0.02	<10	33	<10	6	78
28	X05685	1.9	0.60	<5	210	<5	1.47	1	8	120	1913	3.87	<10	0.31	532	24	0.01	6	1000	24	10	<20	93	0.02	<10	40	<10	4	40
29	X05686	1.3	0.57	<5	205	<5	2.81	1	9	89	1353	3.25	<10	0.31	881	20	0.02	4	1380	24	5	<20	296	0.02	<10	35	<10	4	42
30	X05687	2.7	0.89	<5	115	<5	1.17	1	11	102	2778	3.14	<10	0.47	578	13	0.01	6	1310	30	10	<20	65	<0.01	<10	30	<10	5	47
31	X05688	0.6	0.55	<5	210	<5	3.03	<1	9	106	757	3.24	<10	0.23	983	14	0.02	5	1330	24	<5	<20	595	0.02	<10	35	<10	3	39
32	X05689	0.7	0.83	<5	440	<5	2.70	2	9	133	699	3.82	<10	0.67	1122	13	0.03	7	1090	28	10	<20	283	0.03	<10	54	<10	4	65
33	X05690	1.3	0.93	<5	260	<5	2.27	2	11	85	1175	3.88	<10	0.59	970	17	0.01	8	1260	52	15	<20	154	0.02	<10	42	<10	5	63
34	X05691	1.2	1.04	<5	240	<5	2.05	1	10	138	1497	3.80	<10	0.76	921	15	0.01	6	1060	38	<5	<20	145	0.02	<10	42	<10	4	60
35	X05692	1.5	1.17	<5	430	<5	2.46	2	10	73	1701	4.54	<10	0.87	1072	19	0.02	6	1290	34	15	<20	183	0.02	<10	59	<10	3	83
QC DATA:																													
Repeat:																													
10	X05667	2.9	1.01	5	55	<5	0.63	1	13	163	1730	4.25	<10	0.63	474	19	<0.01	7	940	34	10	<20	55	0.02	<10	19	<10	2	59
19	X05676	1.5	0.90	<5	60	<5	4.62	7	18	121	987	4.67	<10	0.70	1570	19	0.02	7	1080	262	15	<20	317	0.03	<10	47	<10	3	122
Resplit:																													
2	X05659	3.8	1.04	<5	65	<5	0.30	3	13	160	2427	5.37	<10	0.53	309	25	<0.01	12	1070	40	20	<20	24	0.02	<10	20	<10	2	70
Standard:																													
PB113A		11.4	0.29	45	80	<5	1.63	37	2	7	2243	1.05	<10	0.11	1580	66	0.02	3	90	5476	30	<20	88	0.01	<10	8	<10	<1	6916

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5707
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5708

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07211
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	XO5938	<0.03	<0.001
2	XO5939	0.97	0.028
3	XO5940	0.58	0.017
4	XO5941	0.31	0.009
5	XO5942	0.40	0.012
6	XO5943	0.34	0.010
7	XO5944	0.51	0.015
8	XO5945	0.32	0.009
9	XO5946	0.42	0.012
10	XO5947	0.34	0.010
11	XO5948	0.28	0.008
12	XO5949	0.45	0.013
13	XO5950	0.44	0.013
14	XO5951	0.42	0.012
15	XO5952	1.42	0.041
16	XO5953	<0.03	<0.001
17	XO5954	0.59	0.017
18	XO5955	0.40	0.012
19	XO5956	0.35	0.010
20	XO5957	0.31	0.009
21	XO5958	0.35	0.010
22	XO5959	0.44	0.013
23	XO5960	0.28	0.008
24	XO5961	0.27	0.008
25	XO5962	0.48	0.014
26	XO5963	0.64	0.019
27	XO5964	0.38	0.011
28	XO5965	0.31	0.009
29	XO5966	0.31	0.009

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5708 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	XO5967	0.24	0.007
31	XO5968	0.23	0.007
32	XO5969	0.17	0.005
33	XO5970	0.27	0.008
34	XO5971	0.30	0.009
35	XO5972	0.25	0.007
QC DATA:			
Repeat:			
1	XO5938	<0.03	<0.001
2	XO5939	1.00	0.029
10	XO5947	0.34	0.010
15	XO5952	1.41	0.041
19	XO5956	0.34	0.010
Resplits:			
1	XO5938	<0.03	<0.001
Standard:			
OXK48		3.53	0.103

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5708

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07211
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	XO5938	<0.2	3.99	10	225	60	2.50	3	38	35	30	8.44	<10	4.46	1418	15	0.02	10	1030	88	50	<20	176	0.14	<10	245	<10	9	113
2	XO5939	2.9	1.64	<5	170	<5	1.76	2	15	77	2308	5.28	<10	1.54	856	23	0.03	7	1130	48	20	<20	231	0.02	<10	94	<10	4	94
3	XO5940	1.8	1.53	<5	185	<5	1.50	2	13	80	1713	4.53	<10	1.53	921	22	0.04	6	1240	38	20	<20	225	0.02	<10	93	<10	5	83
4	XO5941	0.9	1.59	<5	340	<5	2.71	2	10	46	1067	4.21	<10	2.16	1698	21	0.03	5	1270	36	20	<20	309	0.03	<10	92	<10	6	81
5	XO5942	1.7	1.47	<5	85	<5	1.37	2	15	77	1419	4.68	<10	1.67	1038	27	0.04	7	1260	36	15	<20	165	0.02	<10	97	<10	5	80
6	XO5943	1.5	1.47	<5	180	<5	1.28	2	14	49	1572	4.81	<10	1.58	960	31	0.04	6	1410	38	15	<20	143	0.03	<10	101	<10	7	83
7	XO5944	2.5	1.51	<5	55	<5	2.76	1	12	85	1839	3.91	<10	1.56	1660	20	0.02	6	1200	34	15	<20	242	0.02	<10	64	<10	7	76
8	XO5945	2.4	1.65	<5	65	<5	2.00	2	13	50	1407	4.14	<10	1.89	1522	27	0.01	9	1380	48	35	<20	154	0.02	<10	39	<10	7	91
9	XO5946	2.0	1.55	<5	135	<5	1.10	<1	13	65	1424	3.82	<10	1.47	917	19	0.02	<1	1380	44	<5	<20	107	0.05	<10	49	<10	6	86
10	XO5947	2.0	1.46	5	70	<5	1.40	2	14	39	1352	3.97	<10	1.58	982	27	0.02	4	1380	70	15	<20	145	0.02	<10	51	<10	6	96
11	XO5948	2.8	1.82	<5	105	<5	2.00	2	13	48	1097	4.12	<10	1.93	1474	33	0.03	6	1480	54	25	<20	210	0.03	<10	51	<10	8	130
12	XO5949	4.8	1.48	30	60	<5	1.81	2	15	69	1254	3.75	<10	1.50	1518	30	0.02	5	1460	66	15	<20	155	0.03	<10	31	<10	7	118
13	XO5950	3.8	1.69	20	60	<5	1.84	2	14	68	1294	3.80	<10	1.55	1408	29	0.02	6	1370	60	15	<20	174	0.02	<10	33	<10	5	120
14	XO5951	2.6	1.74	15	85	<5	1.87	2	13	64	1210	3.52	<10	1.62	1280	27	0.02	4	1410	54	20	<20	198	0.03	<10	33	<10	6	96
15	XO5952	6.2	1.07	40	55	<5	2.59	8	14	78	1322	4.37	<10	0.86	1359	41	0.01	11	1230	74	35	<20	146	0.01	<10	24	<10	5	106
16	XO5953	<0.2	0.09	15	<5	<5	>10	<1	2	5	3	0.06	<10	1.96	37	<1	<0.01	<1	50	10	5	<20	6179	0.01	<10	4	<10	<1	<1
17	XO5954	4.6	1.26	65	55	<5	3.38	3	15	61	1744	3.80	<10	1.08	1698	29	0.01	6	1380	44	10	<20	126	0.03	<10	29	<10	6	99
18	XO5955	2.6	1.49	35	60	<5	4.09	2	15	80	1549	4.04	<10	1.18	1876	30	0.01	6	1450	50	10	<20	135	0.03	<10	34	<10	7	105
19	XO5956	1.8	1.21	10	60	<5	4.80	2	14	63	1344	3.28	<10	0.93	1651	21	<0.01	5	1250	32	10	<20	238	0.02	<10	28	<10	5	75
20	XO5957	1.7	1.37	15	55	<5	3.55	1	11	71	1010	3.04	<10	1.03	1256	14	0.01	7	1500	38	20	<20	182	0.02	<10	32	<10	4	75
21	XO5958	2.3	0.96	<5	60	<5	4.90	1	9	50	1471	2.15	<10	0.73	1402	17	<0.01	4	1400	26	10	<20	431	0.02	<10	25	<10	6	62
22	XO5959	4.1	1.03	<5	60	<5	4.75	5	9	63	1626	2.36	<10	0.70	1419	13	0.01	3	1370	64	10	<20	259	0.02	<10	25	<10	6	186
23	XO5960	1.4	1.17	10	115	<5	2.90	1	10	81	1440	2.92	<10	0.87	899	14	0.02	5	1400	36	10	<20	184	0.02	<10	46	<10	6	68
24	XO5961	1.4	1.20	<5	125	<5	2.88	2	10	57	1387	3.73	<10	0.90	936	13	0.02	6	1400	36	10	<20	197	0.02	<10	63	<10	5	75
25	XO5962	2.7	1.17	5	105	<5	2.05	1	10	106	2526	3.37	<10	0.94	723	14	0.03	6	1170	44	10	<20	171	0.02	<10	78	<10	6	79

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	XO5963	2.1	1.28	5	150	<5	2.74	2	11	84	1871	3.43	<10	0.99	898	14	0.03	6	1320	42	15	<20	188	0.02	<10	86	<10	5	83
27	XO5964	2.0	1.33	10	110	<5	5.66	1	8	54	1467	2.70	<10	1.27	2148	13	0.02	4	1300	36	15	<20	232	0.03	<10	37	<10	7	76
28	XO5965	3.2	1.20	20	60	<5	1.03	3	22	62	2704	3.72	20	0.69	204	216	0.04	10	440	78	20	<20	64	0.04	<10	51	<10	6	274
29	XO5966	2.1	1.13	20	75	<5	4.75	2	11	98	1247	3.01	<10	0.86	1580	12	0.02	7	1170	50	20	<20	220	0.02	<10	32	<10	8	71
30	XO5967	1.7	1.21	<5	50	<5	3.70	2	16	57	1009	3.98	<10	0.99	1276	12	0.02	5	1500	36	15	<20	136	0.03	<10	32	<10	6	66
31	XO5968	1.3	1.22	15	95	<5	3.64	1	10	60	956	3.29	<10	0.85	1140	13	0.02	5	1430	38	15	<20	205	0.03	<10	37	<10	7	69
32	XO5969	1.0	1.15	10	260	<5	3.43	<1	9	46	735	3.15	<10	0.77	1101	15	0.03	4	1550	34	10	<20	219	0.03	<10	48	<10	7	73
33	XO5970	1.4	1.38	<5	95	<5	3.87	2	13	43	1131	3.90	<10	1.06	1289	20	0.03	8	1430	42	25	<20	239	0.03	<10	60	<10	6	85
34	XO5971	1.7	0.99	5	110	<5	3.84	<1	9	48	1186	2.22	<10	0.68	1072	21	0.02	2	1350	32	5	<20	233	0.02	<10	33	<10	5	54
35	XO5972	1.6	1.56	20	60	<5	3.77	<1	13	65	876	4.23	<10	1.20	1452	12	0.02	1	1530	56	<5	<20	126	0.06	20	41	<10	6	92
QC DATA:																													
Repeat:																													
1	XO5938	<0.2	3.96	10	245	60	2.47	3	37	35	32	8.30	<10	4.42	1394	15	0.02	9	1020	84	55	<20	178	0.15	<10	243	<10	9	112
10	XO5947	2.3	1.63	10	60	<5	1.54	3	16	44	1470	4.38	<10	1.74	1083	29	0.02	9	1560	78	35	<20	167	0.02	<10	57	<10	7	107
19	XO5956	1.8	1.30	10	60	<5	5.05	2	15	67	1425	3.45	<10	0.99	1739	22	<0.01	6	1300	34	15	<20	273	0.03	<10	30	<10	6	78
Resplit:																													
1	XO5938	<0.2	4.04	<5	230	70	2.65	4	39	33	38	8.54	<10	4.46	1456	13	0.02	12	1040	88	55	<20	167	0.16	<10	247	<10	7	116
Standard:																													
PB113A		11.0	0.29	45	80	<5	1.69	37	3	7	2214	1.08	<10	0.11	1419	62	0.02	3	90	5540	20	<20	89	0.01	<10	8	<10	<1	6971

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5707
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5709

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07196
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05623	0.99	0.029
2	X05624	0.84	0.024
3	X05625	1.28	0.037
4	X05626	0.53	0.015
5	X05627	<0.03	<0.001
6	X05628	0.74	0.022
7	X05629	0.85	0.025
8	X05630	0.83	0.024
9	X05631	0.90	0.026
10	X05632	0.61	0.018
11	X05633	0.56	0.016
12	X05634	0.86	0.025
13	X05635	0.47	0.014
14	X05636	0.89	0.026
15	X05637	0.84	0.024
16	X05638	0.86	0.025
17	X05639	1.84	0.054
18	X05640	0.63	0.018
19	X05641	0.71	0.021
20	X05642	1.38	0.040
21	X05643	<0.03	<0.001
22	X05644	0.73	0.021
23	X05645	0.90	0.026
24	X05646	0.76	0.022
25	X05647	0.82	0.024
26	X05648	1.09	0.032
27	X05649	1.02	0.030
28	X05650	0.81	0.024
29	X05651	0.97	0.028

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5709 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X05652	1.16	0.034
31	X05653	1.57	0.046
32	X05654	0.89	0.026
33	X05655	0.76	0.022
34	X05656	0.66	0.019
35	X05657	1.02	0.030

QC DATA:

Repeat:

1	X05623	0.93	0.027
10	X05632	0.61	0.018
19	X05641	0.74	0.022
20	X05642	1.47	0.043
31	X05653	1.45	0.042

Resplits:

1	X05623	0.87	0.025

Standard:

OXK48		3.57	0.104

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO-TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5709

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07196
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05623	3.1	1.06	10	60	<5	1.09	1	14	86	1929	4.73	<10	0.85	1216	22	<0.01	5	1070	50	10	<20	91	0.03	<10	23	<10	3	77
2	X05624	2.9	1.25	5	70	<5	0.85	2	12	114	2229	4.69	<10	0.94	958	24	<0.01	6	960	46	15	<20	91	0.02	<10	34	<10	2	88
3	X05625	4.3	1.20	10	85	<5	0.76	1	15	148	2934	4.95	<10	0.90	880	24	<0.01	8	670	44	10	<20	104	0.02	<10	41	<10	2	83
4	X05626	2.5	1.58	15	95	<5	1.61	1	12	110	1607	4.13	<10	1.29	1227	27	<0.01	8	1050	54	25	<20	154	0.01	<10	33	<10	4	94
5	X05627	0.2	2.88	10	265	40	4.16	2	28	48	25	6.19	<10	2.40	1499	10	0.01	7	1040	76	35	<20	484	0.04	<10	95	<10	6	95
6	X05628	3.3	1.48	15	65	<5	0.47	2	12	148	2062	4.86	<10	1.06	731	19	<0.01	8	860	48	20	<20	42	0.02	<10	34	<10	<1	85
7	X05629	3.3	1.77	10	110	<5	0.58	2	12	88	2353	4.59	<10	1.34	955	26	<0.01	6	1040	52	20	<20	65	0.02	<10	38	<10	2	114
8	X05630	3.0	1.42	15	75	<5	0.41	1	12	131	1880	4.36	<10	1.04	841	21	<0.01	5	870	48	10	<20	45	0.02	<10	28	<10	1	96
9	X05631	4.9	0.93	30	45	<5	0.55	2	12	137	2609	5.20	<10	0.60	704	33	<0.01	8	820	48	10	<20	47	0.01	<10	22	<10	<1	61
10	X05632	2.3	1.71	10	130	<5	1.59	1	9	110	1588	4.36	<10	1.25	1560	24	<0.01	6	1140	52	15	<20	144	0.02	<10	29	<10	2	117
11	X05633	2.1	1.86	5	160	<5	1.06	2	10	107	1484	4.73	<10	1.33	1278	18	<0.01	6	1230	60	20	<20	141	0.03	<10	30	<10	5	127
12	X05634	3.7	1.40	5	155	<5	1.26	1	10	101	2161	4.49	<10	1.14	1362	33	0.01	6	1030	56	10	<20	159	0.02	<10	30	<10	3	107
13	X05635	2.6	1.44	<5	120	<5	1.21	1	10	115	1360	4.78	<10	1.12	1386	22	0.01	6	970	62	15	<20	169	0.03	<10	33	<10	2	116
14	X05636	4.5	0.89	30	60	<5	0.43	3	14	117	2352	5.25	<10	0.50	495	21	<0.01	7	980	52	10	<20	37	0.01	<10	18	<10	<1	83
15	X05637	3.9	1.01	20	55	<5	0.60	2	12	137	2357	4.84	<10	0.60	641	22	<0.01	9	820	50	15	<20	60	0.01	<10	22	<10	1	83
16	X05638	4.5	0.40	30	70	<5	0.41	2	9	211	2322	5.02	<10	0.16	269	19	<0.01	7	500	40	<5	<20	56	0.03	<10	12	<10	<1	37
17	X05639	4.0	1.19	30	65	<5	1.01	2	22	62	8580	4.22	20	0.61	198	598	0.04	61	110	80	30	<20	66	0.02	<10	45	<10	6	73
18	X05640	4.0	0.99	20	50	<5	0.61	2	12	118	2097	5.38	<10	0.66	608	39	<0.01	7	910	48	5	<20	60	0.02	<10	20	<10	2	87
19	X05641	4.3	1.17	15	55	<5	0.57	2	11	109	2341	5.21	<10	0.77	636	22	<0.01	6	800	54	15	<20	65	0.02	<10	23	<10	2	93
20	X05642	6.2	0.97	10	55	<5	0.32	4	12	174	4037	5.06	<10	0.54	440	26	<0.01	14	390	50	30	<20	36	<0.01	<10	22	<10	<1	86
21	X05643	<0.2	0.02	20	<5	15	>10	<1	1	4	8	0.03	<10	2.56	22	<1	<0.01	<1	70	8	<5	<20	6402	0.01	<10	4	<10	<1	<1
22	X05644	3.8	1.54	10	75	<5	0.66	1	12	130	2351	5.59	<10	1.03	765	18	<0.01	7	990	58	5	<20	68	0.03	<10	28	<10	2	101
23	X05645	4.6	0.75	30	50	<5	0.93	2	15	199	2279	5.30	<10	0.60	773	28	<0.01	9	760	58	<5	<20	82	0.02	<10	18	<10	2	58
24	X05646	3.2	1.58	10	65	<5	1.75	2	14	138	2172	5.12	<10	1.32	1537	24	<0.01	8	920	66	25	<20	210	0.02	<10	33	<10	2	93
25	X05647	4.8	1.38	10	65	<5	0.79	2	15	147	2701	5.88	<10	1.01	860	18	<0.01	8	880	56	15	<20	80	0.02	<10	32	<10	2	105

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05648	5.0	1.33	10	65	<5	0.75	2	13	154	3708	5.09	<10	1.00	975	16	<0.01	9	620	52	20	<20	91	0.01	<10	36	<10	1	107
27	X05649	5.2	1.48	10	70	<5	1.00	2	14	120	3670	5.34	<10	0.96	1067	21	<0.01	7	810	60	15	<20	118	0.02	<10	34	<10	2	115
28	X05650	3.9	1.00	20	50	<5	0.44	2	14	130	2288	5.57	<10	0.61	460	25	<0.01	7	960	46	15	<20	33	0.01	<10	20	<10	<1	74
29	X05651	4.0	0.87	10	55	<5	0.41	2	14	155	2648	4.63	<10	0.47	401	25	<0.01	8	570	40	10	<20	45	0.01	<10	20	<10	<1	61
30	X05652	5.1	0.70	15	50	<5	0.26	1	18	175	3350	4.68	<10	0.34	270	116	<0.01	7	330	34	<5	<20	36	0.01	<10	15	<10	<1	51
31	X05653	6.2	1.12	15	60	<5	0.34	<1	18	136	4947	5.46	<10	0.57	411	25	<0.01	7	270	40	<5	<20	45	<0.01	<10	29	<10	<1	74
32	X05654	3.9	1.24	<5	60	<5	0.71	2	11	142	2817	4.83	<10	0.75	579	16	<0.01	8	800	42	15	<20	85	0.01	<10	24	<10	3	80
33	X05655	4.3	0.71	20	60	<5	0.85	<1	9	184	2372	3.40	<10	0.49	575	136	<0.01	6	340	36	<5	<20	110	0.01	<10	14	<10	2	54
34	X05656	3.7	1.09	15	55	<5	0.25	<1	12	160	2016	4.91	<10	0.56	384	18	<0.01	5	870	46	<5	<20	23	0.02	<10	20	<10	1	95
35	X05657	4.7	1.16	15	55	<5	0.34	2	12	132	2925	5.53	<10	0.69	560	22	<0.01	7	720	50	10	<20	27	0.02	<10	25	<10	1	92
QC DATA:																													
Repeat:																													
1	X05623	3.1	1.14	10	65	<5	1.11	1	14	94	1969	4.82	<10	0.88	1242	25	<0.01	7	1100	52	15	<20	98	0.02	<10	26	<10	3	78
10	X05632	2.1	1.73	5	160	<5	1.57	2	9	114	1593	4.32	<10	1.24	1544	26	<0.01	5	1130	52	20	<20	149	0.03	<10	29	<10	4	116
19	X05641	4.2	1.18	10	70	<5	0.56	1	11	112	2266	5.13	<10	0.75	624	20	<0.01	5	790	54	<5	<20	75	0.02	<10	24	<10	2	92
Resplit:																													
1	X05623	3.3	1.09	5	60	<5	1.21	2	12	96	1872	4.78	<10	0.85	1291	21	<0.01	10	1120	48	10	<20	107	0.02	<10	25	<10	3	77
Standard:																													
Pb113A		11.2	0.29	50	75	<5	1.67	36	2	6	2166	1.07	<10	0.11	1491	62	0.02	5	70	5498	20	<20	89	<0.01	<10	9	<10	<1	6988

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
dl/5707
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5710

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07207
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05798	0.41	0.012
2	X05799	0.39	0.011
3	X05800	0.37	0.011
4	X05801	0.25	0.007
5	X05802	0.57	0.017
6	X05803	0.61	0.018
7	X05804	0.98	0.029
8	X05805	0.82	0.024
9	X05806	0.46	0.013
10	X05807	0.51	0.015
11	X05808	0.51	0.015
12	X05809	0.62	0.018
13	X05810	0.61	0.018
14	X05811	0.51	0.015
15	X05812	0.50	0.015
16	X05813	0.58	0.017
17	X05814	0.44	0.013
18	X05815	0.49	0.014
19	X05816	0.48	0.014
20	X05817	0.66	0.019
21	X05818	0.31	0.009
22	X05819	0.79	0.023
23	X05820	0.62	0.018
24	X05821	0.28	0.008
25	X05822	0.76	0.022
26	X05823	<0.03	<0.001
27	X05824	0.74	0.022
28	X05825	0.51	0.015
29	X05826	0.35	0.010

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5710 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X05827	0.40	0.012
31	X05828	0.65	0.019
32	X05829	0.35	0.010
33	X05830	0.32	0.009
34	X05831	0.46	0.013
35	X05832	0.51	0.015

QC DATA:

Repeat:

1	X05798	0.48	0.014
10	X05807	0.52	0.015
19	X05816	0.49	0.014

Resplits:

1	X05798	0.37	0.011

Standard:

OXK48		3.53	0.103

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5710

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07207
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05798	1.5	0.93	25	215	<5	1.52	<1	9	101	1607	2.36	<10	0.71	492	885	0.03	2	840	38	5	<20	89	0.09	<10	33	<10	5	68
2	X05799	1.5	0.93	15	145	<5	2.25	1	10	88	1754	2.62	<10	0.66	530	127	0.03	4	990	34	10	<20	104	0.08	<10	38	<10	7	56
3	X05800	1.2	0.91	20	135	<5	2.76	1	9	82	1366	2.29	<10	0.55	618	257	0.03	3	1010	32	5	<20	74	0.08	<10	26	<10	6	47
4	X05801	0.9	1.08	20	160	<5	2.96	<1	9	80	975	2.64	<10	0.72	780	285	0.02	1	1040	36	<5	<20	91	0.08	<10	33	<10	7	77
5	X05802	1.3	1.25	5	205	<5	1.21	2	14	61	1286	4.63	<10	0.89	615	43	0.03	6	1500	40	15	<20	96	0.06	<10	58	<10	3	100
6	X05803	1.9	1.20	5	180	<5	2.00	<1	13	74	1891	4.48	<10	0.81	832	31	0.02	5	1360	44	10	<20	226	0.05	<10	53	<10	5	100
7	X05804	2.5	1.14	<5	90	<5	0.97	2	14	101	2218	5.02	<10	0.74	574	38	0.01	7	1160	50	10	<20	76	0.04	<10	48	<10	3	92
8	X05805	2.4	1.07	10	150	<5	2.21	<1	14	55	2147	4.36	<10	0.70	820	34	0.02	4	1500	46	<5	<20	168	0.07	<10	49	<10	6	93
9	X05806	1.7	1.23	10	105	<5	2.59	5	16	53	1319	4.76	<10	1.02	1067	52	0.04	8	1530	48	25	<20	340	0.09	<10	83	<10	5	187
10	X05807	2.7	1.15	25	85	<5	2.43	25	16	60	1681	4.02	<10	0.83	1018	39	0.02	5	1420	80	15	<20	194	0.06	<10	45	<10	5	1676
11	X05808	3.1	1.15	15	95	<5	2.45	28	15	68	1573	4.10	<10	0.86	1034	41	0.02	7	1390	98	25	<20	196	0.06	<10	49	<10	4	1860
12	X05809	2.5	1.28	15	100	<5	2.42	11	14	47	1284	4.13	<10	1.00	1017	35	0.03	5	1540	124	15	<20	233	0.08	<10	58	<10	5	433
13	X05810	1.8	1.18	10	115	<5	2.41	2	14	58	1450	3.92	<10	0.86	920	30	0.02	7	1470	44	10	<20	221	0.06	<10	50	<10	5	112
14	X05811	1.6	1.00	15	105	<5	2.89	2	13	53	1330	3.95	<10	0.59	1033	34	0.01	6	1460	42	10	<20	219	0.04	<10	35	<10	5	86
15	X05812	1.6	0.92	15	90	<5	1.73	1	14	60	1275	4.21	<10	0.45	670	35	<0.01	5	1470	38	<5	<20	114	0.04	<10	32	<10	4	81
16	X05813	2.0	1.02	15	105	<5	2.34	1	15	55	1644	4.19	<10	0.62	938	37	0.01	5	1370	40	10	<20	195	0.06	<10	39	<10	5	79
17	X05814	1.9	1.19	20	110	<5	2.87	4	15	81	1319	4.10	<10	0.72	1165	52	0.01	6	1480	68	15	<20	218	0.06	<10	39	<10	6	227
18	X05815	2.2	1.01	25	85	<5	2.03	1	15	68	1703	3.55	<10	0.56	809	32	<0.01	5	1460	44	5	<20	140	0.05	<10	28	<10	5	78
19	X05816	1.4	0.85	10	120	<5	2.98	<1	14	51	1239	3.93	<10	0.46	963	30	0.02	4	1480	36	<5	<20	257	0.07	<10	45	<10	5	72
20	X05817	1.8	1.14	5	145	<5	2.94	1	16	48	1559	5.28	<10	0.75	1084	34	0.02	7	1490	42	5	<20	226	0.07	<10	56	<10	5	92
21	X05818	3.2	1.27	35	60	<5	1.03	3	22	62	2583	3.70	20	0.63	198	204	0.03	9	510	64	15	<20	52	0.06	<10	49	<10	6	278
22	X05819	2.4	1.13	25	95	<5	2.59	2	13	63	2851	4.49	<10	0.74	944	68	<0.01	8	1350	42	20	<20	165	0.05	<10	42	<10	3	70
23	X05820	2.1	1.15	10	95	<5	2.90	2	15	54	1639	4.54	<10	0.83	971	40	0.02	6	1440	58	15	<20	250	0.08	<10	60	<10	4	86
24	X05821	0.9	1.24	15	180	<5	2.87	<1	13	61	763	4.61	<10	0.88	1007	23	0.03	5	1540	50	10	<20	203	0.09	<10	63	<10	3	90
25	X05822	1.5	1.21	<5	95	<5	1.45	3	15	76	1666	5.41	<10	0.89	686	41	0.03	12	1250	42	40	<20	121	0.04	<10	75	<10	2	72

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05823	<0.2	0.02	25	<5	<5	>10	<1	1	3	5	0.04	<10	1.66	39	<1	<0.01	<1	40	4	5	<20	6055	0.01	<10	4	<10	<1	<1
27	X05824	2.6	0.88	15	55	<5	1.93	2	14	158	2952	4.45	<10	0.50	783	46	<0.01	8	580	44	10	<20	114	0.03	<10	31	<10	3	71
28	X05825	2.1	0.84	15	70	<5	2.08	<1	13	80	1757	3.34	<10	0.42	772	47	<0.01	5	1400	32	10	<20	144	0.03	<10	26	<10	6	50
29	X05826	1.5	0.93	30	65	<5	1.45	1	16	103	1100	3.32	<10	0.52	542	40	0.01	6	1370	38	5	<20	99	0.04	<10	30	<10	3	57
30	X05827	1.9	1.10	20	80	<5	3.00	1	14	60	1271	3.63	<10	0.75	1016	35	0.02	5	1420	62	10	<20	195	0.06	<10	42	<10	4	91
31	X05828	1.9	1.27	15	80	<5	1.78	1	13	88	1705	4.17	<10	1.07	660	78	0.04	6	1260	42	15	<20	141	0.07	<10	68	<10	4	55
32	X05829	1.1	1.28	20	80	<5	2.64	<1	15	61	1083	4.50	<10	1.07	869	103	0.02	5	1370	48	15	<20	281	0.09	<10	71	<10	5	56
33	X05830	1.0	0.97	10	160	<5	2.80	2	13	64	906	4.19	<10	0.75	903	37	0.03	8	1480	32	20	<20	273	0.08	<10	78	<10	4	58
34	X05831	1.5	1.08	<5	140	<5	3.75	2	14	46	1114	4.24	<10	0.89	1147	31	0.04	5	1470	40	15	<20	368	0.10	<10	83	<10	4	70
35	X05832	1.9	1.12	20	95	<5	3.06	<1	14	75	1536	4.34	<10	0.86	1033	34	0.03	5	1300	38	10	<20	265	0.09	<10	69	<10	4	66
QC DATA:																													
Repeat:																													
1	X05798	1.5	1.00	20	230	<5	1.59	<1	9	109	1509	2.46	<10	0.74	512	923	0.03	2	870	40	<5	<20	103	0.09	<10	36	<10	5	70
10	X05807	2.7	1.19	25	95	<5	2.42	25	16	63	1659	4.01	<10	0.82	1011	34	0.02	5	1420	80	15	<20	194	0.07	<10	47	<10	4	1679
19	X05816	1.4	0.94	10	120	<5	3.06	1	15	55	1297	4.05	<10	0.49	997	32	0.02	6	1470	36	5	<20	265	0.07	<10	49	<10	5	71
Resplit:																													
1	X05798	1.1	1.09	25	240	<5	1.60	1	10	108	1486	2.66	<10	0.81	550	1200	0.04	3	960	42	5	<20	98	0.08	<10	39	<10	6	74
Standard:																													
Pb113A		10.9	0.24	40	65	<5	1.73	37	3	6	2206	1.11	<10	0.11	1438	69	0.02	4	90	5526	15	<20	89	<0.01	<10	9	<10	<1	6984

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5707
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5711

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07206
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X14178	<0.03	<0.001
2	X14179	<0.03	<0.001
3	X14180	0.23	0.007
4	X14181	0.17	0.005
5	X14182	<0.03	<0.001
6	X14183	0.20	0.006
7	X14184	0.25	0.007
8	X14185	0.27	0.008
9	X14186	0.38	0.011
10	X14187	0.35	0.010
11	X14188	0.16	0.005
12	X14189	0.29	0.008
13	X14190	0.40	0.012
14	X14191	0.43	0.013
15	X14192	0.27	0.008
16	X14193	0.39	0.011
17	X14194	0.28	0.008
18	X14195	0.12	0.003
19	X14196	0.41	0.012
20	X14197	0.33	0.010
21	X14198	0.25	0.007
22	X14199	0.16	0.005
23	X14200	1.87	0.055
24	X14201	0.21	0.006
25	X14202	0.22	0.006
26	X14203	0.18	0.005
27	X14204	0.22	0.006
28	X14205	0.23	0.007
29	X14206	<0.03	<0.001

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5711 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X14207	0.29	0.008
31	X14208	0.77	0.022
32	X14209	0.74	0.022
33	X14210	0.46	0.013
34	X14176	0.32	0.009
35	X14177	0.26	0.008

QC DATA:

Repeat:

1	X14178	<0.03	<0.001
10	X14187	0.29	0.008
19	X14196	0.46	0.013

Resplits:

1	X14178	<0.03	<0.001

Standard:

OXK48		3.54	0.103

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5711

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07206
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X14178	<0.2	4.22	45	80	<5	6.24	3	34	142	62	5.37	<10	3.95	1305	<1	0.03	78	600	4	<5	<20	99	0.09	<10	116	<10	8	62
2	X14179	<0.2	4.59	50	100	<5	5.15	3	33	185	68	5.61	<10	4.14	1392	<1	0.03	91	570	10	<5	<20	95	0.06	<10	120	<10	8	93
3	X14180	0.7	1.71	30	50	<5	0.46	3	16	85	814	5.49	<10	1.27	338	95	0.04	3	1680	14	<5	<20	26	<0.01	<10	28	<10	4	53
4	X14181	0.7	1.40	25	50	<5	0.52	6	16	100	715	5.22	<10	1.02	273	116	0.04	2	1540	30	<5	<20	31	<0.01	<10	24	<10	4	83
5	X14182	<0.2	4.74	55	105	<5	2.92	4	26	52	8	7.66	<10	3.49	1580	7	0.02	<1	1230	4	<5	<20	91	<0.01	<10	192	<10	8	107
6	X14183	0.3	2.52	35	60	<5	0.61	3	13	75	492	5.66	<10	1.89	732	56	0.04	1	1830	6	<5	<20	21	<0.01	<10	62	<10	5	88
7	X14184	0.4	1.54	25	50	<5	0.53	3	15	81	692	5.81	<10	1.13	414	31	0.04	2	1920	22	<5	<20	16	<0.01	<10	29	<10	4	72
8	X14185	0.5	1.34	20	45	<5	0.41	2	16	87	696	4.80	<10	1.01	403	87	0.03	2	1780	30	<5	<20	12	<0.01	<10	22	<10	4	67
9	X14186	0.7	1.41	30	45	<5	0.48	4	16	102	784	5.12	<10	1.11	474	66	0.03	2	1700	30	5	<20	14	<0.01	<10	23	<10	4	89
10	X14187	0.4	1.02	20	45	<5	0.63	2	18	85	722	4.69	<10	0.78	383	78	0.03	1	1650	26	<5	<20	13	<0.01	<10	13	<10	2	55
11	X14188	0.5	0.96	30	40	<5	0.93	2	14	99	632	3.89	<10	0.71	400	28	0.03	3	1700	16	5	<20	19	<0.01	<10	11	<10	4	38
12	X14189	0.6	0.99	20	40	<5	0.67	2	13	80	705	4.75	<10	0.77	290	29	0.03	2	1770	14	<5	<20	18	<0.01	<10	12	<10	3	29
13	X14190	3.4	1.22	50	45	<5	0.51	3	15	88	646	4.98	<10	0.95	277	62	0.03	2	1730	18	15	<20	13	<0.01	<10	21	<10	3	47
14	X14191	9.4	0.80	70	45	<5	0.40	3	14	103	720	5.06	<10	0.52	177	19	0.03	2	1540	18	35	<20	12	<0.01	<10	9	<10	2	56
15	X14192	2.0	1.43	35	50	<5	0.44	3	14	87	631	5.23	<10	1.16	314	33	0.03	2	1750	26	<5	<20	13	<0.01	<10	24	<10	3	75
16	X14193	2.3	1.26	40	45	<5	0.40	3	17	96	601	5.19	<10	0.95	257	43	0.03	2	1750	20	10	<20	12	<0.01	<10	22	<10	3	74
17	X14194	1.2	1.08	20	45	<5	0.40	2	14	81	455	4.71	<10	0.78	197	141	0.03	2	1650	12	<5	<20	11	<0.01	<10	13	<10	3	42
18	X14195	0.6	0.75	15	40	<5	0.55	2	12	94	332	4.05	<10	0.45	173	46	0.03	2	1540	26	<5	<20	13	<0.01	<10	8	<10	2	18
19	X14196	1.1	0.84	30	40	<5	0.41	2	13	81	641	4.32	<10	0.52	151	37	0.03	2	1670	10	<5	<20	11	<0.01	<10	10	<10	3	25
20	X14197	0.8	1.05	25	45	<5	0.89	3	13	80	541	4.88	<10	0.76	384	104	0.03	2	1680	22	<5	<20	31	<0.01	<10	16	<10	4	41
21	X14198	0.6	1.04	20	45	<5	0.72	2	11	86	611	4.10	<10	0.78	367	50	0.03	2	1680	16	<5	<20	15	<0.01	<10	15	<10	3	31
22	X14199	0.7	0.67	25	45	<5	0.85	3	13	100	362	4.68	<10	0.40	336	117	0.02	1	1380	30	10	<20	15	<0.01	<10	8	<10	2	22
23	X14200	4.0	1.18	40	50	<5	1.03	4	19	50	8710	4.09	20	0.59	203	611	0.04	65	620	48	20	<20	64	0.04	<10	36	<10	8	75
24	X14201	0.4	0.91	15	45	<5	0.83	2	14	73	552	4.43	<10	0.63	380	77	0.03	2	1610	14	<5	<20	16	<0.01	<10	9	<10	2	39
25	X14202	0.3	0.94	15	45	<5	0.67	2	12	89	457	4.40	<10	0.66	323	58	0.03	2	1640	14	<5	<20	14	<0.01	<10	9	<10	2	42

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X14203	0.6	1.11	15	45	<5	0.73	2	15	79	549	4.45	<10	0.87	379	158	0.03	2	1640	16	<5	<20	14	<0.01	<10	13	<10	3	37
27	X14204	1.1	1.06	40	45	<5	0.63	3	13	81	664	4.54	<10	0.87	323	46	0.03	1	1510	18	20	<20	13	<0.01	<10	12	<10	2	34
28	X14205	4.2	1.55	70	45	<5	1.02	6	14	89	584	4.96	<10	1.37	597	48	0.03	2	1630	58	35	<20	19	<0.01	<10	24	<10	4	76
29	X14206	<0.2	0.02	<5	<5	<5	>10	<1	<1	1	<1	0.01	<10	1.76	18	<1	<0.01	<1	60	<2	<5	<20	6013	<0.01	<10	<1	<10	<1	<1
30	X14207	1.9	1.03	25	45	<5	0.95	3	12	83	445	4.72	<10	0.80	375	28	0.03	2	1590	26	5	<20	21	<0.01	<10	14	<10	3	38
31	X14208	8.7	0.94	45	45	<5	0.91	5	12	97	411	5.09	<10	0.64	316	29	0.03	2	1610	36	25	<20	49	<0.01	<10	15	<10	3	52
32	X14209	12.8	0.70	50	40	<5	0.97	5	10	97	419	5.04	<10	0.42	301	93	0.03	<1	1560	54	40	<20	28	<0.01	<10	7	<10	2	47
33	X14210	3.5	1.02	30	40	<5	0.70	3	14	97	575	4.32	<10	0.63	275	26	0.03	2	1710	6	<5	<20	14	<0.01	<10	12	<10	4	43
34	X14176	0.7	1.44	20	45	<5	0.41	3	13	82	895	4.67	<10	1.09	288	63	0.04	2	1750	20	<5	<20	21	<0.01	<10	21	<10	3	51
35	X14177	0.7	1.48	45	50	<5	0.54	3	15	86	800	4.45	<10	0.97	282	101	0.04	3	1660	4	<5	<20	42	<0.01	<10	24	<10	3	45
QC DATA:																													
Repeat:																													
1	X14178	<0.2	4.29	45	80	<5	6.34	3	34	140	65	5.46	<10	4.04	1295	<1	0.04	78	600	6	<5	<20	99	0.09	<10	120	<10	8	63
10	X14187	0.4	1.07	25	45	<5	0.65	3	19	89	747	4.78	<10	0.79	401	82	0.03	1	1720	26	<5	<20	14	<0.01	<10	13	<10	3	56
19	X14196	1.1	0.85	25	40	<5	0.40	3	12	81	651	4.28	<10	0.52	147	34	0.03	2	1640	10	<5	<20	12	<0.01	<10	10	<10	3	26
Resplit:																													
1	X14178	<0.2	4.50	50	85	<5	6.50	4	36	147	71	5.57	<10	4.15	1289	<1	0.04	80	620	4	<5	<20	97	0.10	<10	124	<10	7	68
Standard:																													
PB113A		11.9	0.24	50	70	<5	1.79	41	2	2	2306	1.04	<10	0.11	1469	57	0.02	1	100	5606	<5	<20	84	0.01	<10	7	<10	1	6995

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/n5711S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5712

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07208
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05833	0.51	0.015
2	X05834	0.53	0.015
3	X05835	0.43	0.013
4	X05836	0.31	0.009
5	X05837	0.36	0.010
6	X05838	0.35	0.010
7	X05839	0.27	0.008
8	X05840	0.26	0.008
9	X05841	0.38	0.011
10	X05842	0.34	0.010
11	X05843	0.41	0.012
12	X05844	0.28	0.008
13	X05845	0.25	0.007
14	X05846	0.55	0.016
15	X05847	0.77	0.022
16	X05848	0.73	0.021
17	X05849	0.70	0.020
18	X05850	0.50	0.015
19	X05851	0.38	0.011
20	X05852	0.72	0.021
21	X05853	0.51	0.015
22	X05854	0.34	0.010
23	X05855	0.33	0.010
24	X05856	0.36	0.010
25	X05857	<0.03	<0.001
26	X05858	0.98	0.029
27	X05859	0.43	0.013
28	X05860	0.64	0.019
29	X05861	1.09	0.032

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5712 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X05862	0.62	0.018
31	X05863	0.37	0.011
32	X05864	0.55	0.016
33	X05865	0.56	0.016
34	X05866	0.77	0.022
35	X05867	0.72	0.021
QC DATA:			
Repeat:			
1	X05833	0.52	0.015
10	X05842	0.34	0.010
19	X05851	0.38	0.011
Resplits:			
1	X05833	0.52	0.015
Standard:			
OXK48		3.52	0.103

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5712

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07208
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05833	2.2	1.09	15	125	<5	2.64	3	11	55	1841	3.95	<10	0.80	1322	29	0.02	3	1963	16	<5	<20	108	0.04	<10	33	<10	6	122
2	X05834	7.4	0.97	60	60	<5	3.30	3	11	48	1507	3.69	<10	0.69	1765	28	0.02	3	1963	28	<5	<20	117	0.04	<10	31	<10	6	139
3	X05835	2.7	1.06	15	75	<5	1.67	3	11	69	1656	3.85	<10	0.81	1066	28	0.03	3	2080	18	<5	<20	87	0.06	<10	57	<10	7	136
4	X05836	1.3	1.00	15	110	<5	2.33	3	11	61	1061	4.03	<10	0.82	1292	26	0.04	3	2015	14	<5	<20	121	0.07	<10	65	<10	6	109
5	X05837	2.7	1.03	20	125	<5	2.74	3	10	59	1251	4.11	<10	0.81	1467	22	0.04	3	2054	60	<5	<20	152	0.06	<10	62	<10	6	139
6	X05838	1.8	1.18	20	115	<5	2.20	3	12	54	1474	4.10	<10	0.97	1325	24	0.05	3	2119	48	<5	<20	107	0.07	<10	65	<10	6	185
7	X05839	1.4	1.31	15	175	<5	1.41	2	13	61	1063	4.96	<10	1.18	1354	26	0.04	3	2184	6	<5	<20	67	0.08	<10	89	<10	6	141
8	X05840	1.4	1.09	15	205	<5	1.52	2	12	59	1140	4.91	<10	0.91	1262	33	0.04	3	2249	8	<5	<20	72	0.09	<10	93	<10	6	129
9	X05841	1.9	1.02	15	155	<5	1.55	2	10	54	1308	3.68	<10	0.79	1125	31	0.03	3	2249	8	<5	<20	76	0.07	<10	56	<10	6	138
10	X05842	1.7	1.25	15	105	<5	1.19	2	13	52	1368	4.14	<10	1.09	1363	52	0.04	3	2184	8	<5	<20	63	0.09	<10	75	<10	6	131
11	X05843	2.1	1.10	15	110	<5	1.56	2	12	57	1428	4.55	<10	0.92	1181	25	0.04	2	2015	14	<5	<20	57	0.08	<10	76	<10	6	139
12	X05844	1.6	1.20	10	260	<5	1.42	2	11	56	1069	4.62	<10	1.07	1160	19	0.04	2	2067	4	<5	<20	56	0.07	<10	93	<10	5	116
13	X05845	1.3	1.09	15	250	<5	0.89	2	11	66	1103	3.79	<10	0.94	1050	21	0.05	3	1937	10	<5	<20	117	0.08	<10	72	<10	5	109
14	X05846	1.7	0.97	10	255	<5	2.11	2	10	50	1393	4.35	<10	0.76	1233	27	0.03	2	1989	8	<5	<20	83	0.07	<10	68	<10	6	94
15	X05847	3.2	0.95	20	55	<5	2.47	2	10	82	2128	4.39	<10	0.73	1242	20	0.03	2	1534	32	<5	<20	68	0.06	<10	60	<10	6	100
16	X05848	2.6	1.15	20	60	<5	2.16	2	11	74	2122	4.55	<10	1.00	1310	18	0.03	2	1508	12	<5	<20	60	0.05	<10	59	<10	6	114
17	X05849	1.8	1.26	15	105	<5	1.71	2	10	62	1699	4.99	<10	1.14	1266	18	0.04	2	1742	10	<5	<20	56	0.07	<10	85	<10	6	105
18	X05850	2.1	1.42	15	100	<5	1.70	2	11	63	1697	4.46	<10	1.33	1370	35	0.04	2	1833	10	<5	<20	63	0.07	<10	83	<10	6	114
19	X05851	1.4	1.25	15	120	<5	1.34	3	10	67	1174	4.28	<10	1.22	1066	35	0.04	2	1677	8	<5	<20	55	0.07	<10	80	<10	6	119
20	X05852	2.6	1.09	15	65	<5	2.40	2	9	61	1976	3.53	<10	0.85	1195	25	0.02	2	1716	12	<5	<20	49	0.04	<10	47	<10	7	88
21	X05853	1.8	1.13	15	80	<5	1.89	2	9	54	1440	3.66	<10	0.96	1024	20	0.03	2	1625	10	<5	<20	49	0.06	<10	52	<10	5	80
22	X05854	1.7	1.30	15	80	<5	1.72	2	10	48	1353	3.51	<10	1.17	1178	24	0.05	3	1872	6	<5	<20	70	0.07	<10	67	<10	6	97
23	X05855	1.2	1.34	10	175	<5	1.20	2	9	42	1110	3.66	<10	1.27	1104	17	0.05	3	1794	2	<5	<20	44	0.07	<10	71	<10	5	88
24	X05856	1.5	1.36	10	125	<5	1.60	2	10	44	1230	3.38	<10	1.32	1070	22	0.05	2	1677	6	<5	<20	50	0.06	<10	60	<10	5	77
25	X05857	<0.2	0.03	<5	<5	<5	>10	<1	<1	2	3	0.03	<10	1.43	24	<1	0.01	<1	52	<2	<5	<20	4826	<0.01	<10	<1	<10	<1	46

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05858	3.7	1.19	50	45	5	0.67	3	11	44	3365	3.10	20	0.57	280	219	0.05	14	390	116	25	<20	31	0.02	<10	30	<10	7	171
27	X05859	2.3	1.15	20	50	<5	2.02	2	8	49	1399	3.05	<10	0.92	1132	17	0.02	3	1560	8	<5	<20	46	0.04	<10	28	<10	5	73
28	X05860	3.3	1.05	10	80	<5	1.83	2	7	46	2143	4.03	<10	0.88	904	18	0.04	2	1469	10	<5	<20	61	0.04	<10	42	<10	5	60
29	X05861	14.5	1.16	20	50	<5	1.14	3	9	65	3317	5.06	<10	0.98	821	16	0.04	1	1339	46	<5	<20	32	0.04	<10	59	10	5	80
30	X05862	2.3	1.06	10	55	<5	1.53	2	8	77	2025	3.33	<10	0.91	848	15	0.04	2	1391	12	<5	<20	65	0.04	<10	43	<10	5	73
31	X05863	1.4	0.87	10	90	<5	1.60	2	7	44	1084	3.37	<10	0.72	795	35	0.04	2	1547	8	<5	<20	78	0.04	<10	45	<10	5	54
32	X05864	2.0	0.85	10	40	<5	1.78	2	8	57	1560	3.21	<10	0.64	909	16	0.03	2	1300	12	<5	<20	51	0.03	<10	28	<10	5	48
33	X05865	1.9	1.01	10	70	<5	1.69	2	8	43	1676	3.02	<10	0.86	839	17	0.04	2	1534	8	<5	<20	63	0.05	<10	34	<10	6	58
34	X05866	2.6	0.92	10	40	<5	2.05	2	8	65	2136	2.97	<10	0.78	988	23	0.03	2	1196	12	<5	<20	58	0.03	<10	23	<10	5	48
35	X05867	2.1	0.92	10	45	<5	1.75	2	9	51	1575	3.15	<10	0.79	815	43	0.03	2	1222	8	<5	<20	75	0.04	<10	29	<10	5	49
QC DATA:																													
Repeat:																													
1	X05833	2.2	1.07	15	120	<5	2.78	2	12	56	1772	3.08	<10	0.80	1216	32	0.02	3	1560	10	<5	<20	106	0.05	<10	33	<10	6	114
10	X05842	1.7	1.30	15	100	<5	1.11	2	12	50	1406	3.90	<10	1.11	1313	51	0.04	3	1900	8	<5	<20	59	0.09	<10	72	<10	6	122
19	X05851	1.6	1.27	10	100	<5	1.19	3	8	57	1204	3.94	<10	1.32	1052	30	0.05	2	1520	8	<5	<20	45	0.06	<10	77	<10	5	105
Resplit:																													
1	X05833	2.2	1.13	10	100	<5	2.70	1	9	45	1840	3.75	<10	0.92	792	33	0.03	2	1430	10	<5	<20	90	0.03	<10	27	<10	6	86
Standard:																													
Pb113A		11.4	0.30	45	50	<5	1.22	22	1	<1	2259	1.01	<10	0.12	1459	65	0.02	<1	100	5438	5	<20	85	<0.01	<10	4	<10	1	6930

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5711
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5713

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Revised 5-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07204
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X14106	0.92	0.027
2	X14107	0.64	0.019
3	X14108	1.14	0.033
4	X14109	1.34	0.039
5	X14110	0.80	0.023
6	X14111	0.22	0.006
7	X14112	1.46	0.043
8	X14113	0.73	0.021
9	X14114	1.63	0.048
10	X14115	1.98	0.058
11	X14116	0.73	0.021
12	X14117	0.75	0.022
13	X14118	1.17	0.034
14	X14119	0.97	0.028
15	X14120	1.01	0.029
16	X14121	1.00	0.029
17	X14122	1.04	0.030
18	X14123	1.14	0.033
19	X14124	1.06	0.031
20	X14125	0.65	0.019
21	X14126	1.00	0.029
22	X14127	0.88	0.026
23	X14128	0.44	0.013
24	X14129	0.56	0.016
25	X14130	0.38	0.011
26	X14131	0.47	0.014
27	X14132	0.30	0.009
28	X14133	0.72	0.021
29	X14134	0.63	0.018

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5713 5-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X14135	0.61	0.018
31	X14136	0.69	0.020
32	X14137	0.13	0.004
33	X14138	<0.03	<0.001
34	X14139	1.82	0.053
35	X14140	<0.03	<0.001
QC DATA:			
Repeats			
1	X14106	0.87	0.025
4	X14109	1.39	0.041
9	X14114	1.54	0.045
10	X14115	2.01	0.059
19	X14124	1.03	0.030
Resplits:			
1	X14106	1.02	0.030
Standard:			
OXK48		3.51	0.102

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5713

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07204
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X14106	1.9	0.47	35	25	<5	0.12	2	7	186	1121	3.45	<10	0.23	109	56	0.03	8	540	84	10	<20	7	<0.01	<10	4	<10	<1	133
2	X14107	1.3	0.34	15	30	<5	0.19	3	10	84	1621	3.74	<10	0.06	46	60	0.03	10	1080	90	<5	<20	7	<0.01	<10	3	<10	2	173
3	X14108	1.4	0.40	5	30	<5	0.14	2	9	81	1559	4.33	<10	0.13	71	72	0.04	10	810	32	<5	<20	7	<0.01	<10	3	<10	1	52
4	X14109	2.5	0.30	10	35	<5	0.16	2	11	102	2301	5.16	<10	0.03	36	91	0.04	12	920	14	<5	<20	8	<0.01	<10	2	<10	1	37
5	X14110	1.4	0.47	5	25	<5	0.11	2	6	124	1011	2.85	<10	0.22	92	51	0.03	10	530	64	<5	<20	6	<0.01	<10	3	<10	<1	79
6	X14111	2.0	0.63	25	25	<5	0.11	2	5	167	1143	2.76	<10	0.36	146	70	0.03	7	390	82	<5	<20	5	<0.01	<10	5	<10	<1	94
7	X14112	3.2	0.32	45	30	<5	0.09	2	9	105	2521	4.18	<10	0.10	54	202	0.03	8	510	44	10	<20	6	<0.01	<10	2	<10	<1	35
8	X14113	2.3	0.47	25	30	<5	0.18	2	9	141	1730	4.28	<10	0.18	109	71	0.04	10	950	40	5	<20	11	<0.01	<10	4	<10	1	34
9	X14114	3.2	0.41	15	30	<5	0.14	2	10	93	2494	4.72	<10	0.16	95	62	0.04	8	770	24	<5	<20	10	<0.01	<10	3	<10	1	38
10	X14115	3.7	0.49	105	35	<5	0.16	3	11	112	2705	5.24	<10	0.21	116	52	0.04	9	830	44	25	<20	14	<0.01	<10	3	<10	1	73
11	X14116	2.7	0.43	200	30	<5	0.20	3	11	89	1832	4.78	<10	0.17	115	70	0.04	9	990	66	45	<20	16	<0.01	<10	2	<10	1	91
12	X14117	3.2	0.36	20	25	<5	0.12	1	8	146	1766	3.49	<10	0.08	70	89	0.03	7	670	20	<5	<20	13	<0.01	<10	1	<10	<1	17
13	X14118	2.7	0.48	10	30	<5	0.13	2	9	126	1983	3.96	<10	0.22	117	59	0.04	8	710	24	<5	<20	8	<0.01	<10	3	<10	1	39
14	X14119	2.5	0.48	15	30	<5	0.12	2	11	157	1902	4.42	<10	0.14	118	77	0.04	11	720	14	<5	<20	8	<0.01	<10	5	<10	2	44
15	X14120	2.6	0.53	10	30	<5	0.13	2	9	107	2269	4.10	<10	0.22	120	62	0.03	9	740	34	<5	<20	8	<0.01	<10	3	<10	1	79
16	X14121	2.3	0.45	10	30	<5	0.13	2	9	136	1654	4.59	<10	0.11	74	139	0.04	8	770	24	<5	<20	8	<0.01	<10	3	<10	1	41
17	X14122	2.6	0.43	15	30	<5	0.12	2	12	117	2181	4.57	<10	0.13	85	65	0.04	10	670	16	<5	<20	9	<0.01	<10	2	<10	1	84
18	X14123	2.3	0.45	15	25	<5	0.16	2	8	170	1545	3.91	<10	0.10	94	74	0.04	10	760	22	<5	<20	21	<0.01	<10	3	<10	2	35
19	X14124	2.1	0.41	10	25	<5	0.17	2	8	84	1775	3.80	<10	0.15	107	101	0.04	8	640	26	<5	<20	54	<0.01	<10	3	<10	1	47
20	X14125	2.0	0.60	20	25	<5	0.26	2	7	134	1195	3.38	<10	0.23	156	102	0.04	10	890	42	<5	<20	36	<0.01	<10	4	<10	2	67
21	X14126	2.2	0.62	15	30	<5	0.22	2	9	83	1403	4.47	<10	0.27	117	58	0.04	11	1210	18	<5	<20	14	<0.01	<10	4	<10	3	43
22	X14127	1.7	0.66	10	25	<5	0.09	2	8	125	1344	3.82	<10	0.26	108	48	0.03	9	430	24	<5	<20	9	<0.01	<10	4	<10	1	35
23	X14128	1.2	0.59	5	25	<5	0.04	1	7	100	1529	2.79	<10	0.28	90	79	0.03	6	150	36	<5	<20	8	<0.01	<10	2	<10	<1	41
24	X14129	1.1	0.52	10	20	<5	0.05	1	7	195	1564	2.62	<10	0.21	91	49	0.03	7	160	30	<5	<20	9	<0.01	<10	2	<10	<1	30
25	X14130	1.2	0.56	10	30	<5	0.21	2	9	158	1762	3.39	<10	0.25	165	66	0.02	7	830	30	<5	<20	15	<0.01	<10	3	<10	<1	73

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X14131	1.7	0.64	10	35	<5	0.12	3	10	190	1488	4.28	<10	0.29	191	53	0.02	9	370	38	<5	<20	15	<0.01	<10	3	<10	<1	91
27	X14132	2.1	1.04	15	40	<5	0.16	3	7	215	1045	3.56	<10	0.65	372	62	0.02	12	530	1016	<5	<20	12	<0.01	<10	11	<10	<1	207
28	X14133	2.6	1.12	20	45	<5	0.19	4	11	191	1341	6.07	<10	0.64	353	57	0.02	17	840	116	<5	<20	19	<0.01	<10	12	<10	1	220
29	X14134	1.9	1.26	40	45	<5	0.28	3	12	117	746	5.62	<10	0.72	396	86	0.02	17	1320	16	<5	<20	18	<0.01	<10	13	<10	3	219
30	X14135	2.3	1.54	40	50	<5	0.27	4	14	157	1132	5.89	<10	0.93	479	72	0.03	18	1240	24	<5	<20	18	<0.01	<10	19	<10	3	268
31	X14136	3.1	0.74	45	40	<5	0.23	3	15	137	1367	5.13	<10	0.32	186	79	0.03	16	990	20	<5	<20	21	<0.01	<10	8	<10	2	67
32	X14137	1.1	4.85	80	90	<5	0.27	5	28	76	351	8.97	<10	3.48	1452	18	0.02	3	1310	14	<5	<20	14	<0.01	<10	188	<10	4	241
33	X14138	<0.2	5.67	80	80	<5	0.30	5	25	37	14	8.24	<10	4.12	1669	<1	0.02	<1	1460	16	<5	<20	10	<0.01	<10	241	<10	7	230
34	X14139	4.2	1.15	35	50	<5	1.05	4	19	59	8576	4.20	20	0.61	210	583	0.04	65	620	50	25	<20	61	0.04	<10	37	<10	8	73
35	X14140	<0.2	0.02	<5	<5	<5	>10	<1	<1	1	9	0.03	<10	1.46	31	<1	<0.01	<1	40	2	<5	<20	5781	<0.01	<10	1	<10	<1	<1
QC DATA:																													
Repeat:																													
1	X14106	2.0	0.45	35	25	<5	0.11	2	7	179	1104	3.53	<10	0.23	104	51	0.03	8	530	78	5	<20	7	<0.01	<10	4	<10	<1	123
10	X14115	3.6	0.49	105	30	<5	0.18	3	11	114	2790	5.45	<10	0.21	119	55	0.04	10	860	46	25	<20	14	<0.01	<10	3	<10	1	74
19	X14124	2.1	0.39	15	35	<5	0.18	3	10	109	1816	4.18	<10	0.13	168	128	0.02	9	820	30	<5	<20	61	<0.01	<10	4	<10	2	49
Resplit:																													
1	X14106	2.1	0.43	50	35	<5	0.14	6	11	219	1202	3.64	<10	0.18	130	60	0.02	11	610	90	5	<20	10	<0.01	<10	5	<10	<1	146
Standard:																													
Pb113A		11.6	0.26	45	60	<5	1.77	38	2	2	2215	1.02	<10	0.11	1490	69	0.01	<1	100	5598	5	<20	86	0.01	<10	6	<10	1	6917

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

Kgru Bruce /pos

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5711
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5714

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07236
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X14351	0.51	0.015
2	X14352	0.31	0.009
3	X14353	0.37	0.011
4	X14354	0.31	0.009
5	X14355	0.81	0.024
6	X14356	0.54	0.016
7	X14357	0.32	0.009
8	X14358	0.99	0.029
9	X14359	0.40	0.012
10	X14360	1.61	0.047
11	X14361	0.32	0.009
12	X14362	0.34	0.010
13	X14363	0.42	0.012
14	X14364	0.42	0.012
15	X14365	0.46	0.013
16	X14366	0.37	0.011
17	X14367	0.36	0.010
18	X14368	0.32	0.009
19	X14369	0.38	0.011
20	X14370	0.25	0.007
21	X14371	0.34	0.010
22	X14372	0.66	0.019
23	X14373	0.31	0.009
24	X14374	0.80	0.023
25	X14375	<0.03	<0.001
26	X14376	0.27	0.008
27	X14377	0.44	0.013
28	X14378	0.28	0.008
29	X14379	0.25	0.007

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5714 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X14380	0.22	0.006
31	X14381	0.16	0.005
32	X14382	0.39	0.011
33	X14383	0.44	0.013
34	X14384	0.32	0.009
35	X14385	0.37	0.011

QC DATA:

Repeat:

1	X14351	0.49	0.014
10	X14360	1.60	0.047
19	X14369	0.37	0.011


Resplits:

1	X14351	0.47	0.014

Standard:

OXK48		3.56	0.104

AU: 30g FA/AA-Finish



ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 2007-5714

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07236
Submitted by: Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X14351	1.4	1.21	10	95	<5	1.16	2	10	70	1393	3.14	<10	0.95	372	43	0.04	4	1590	10	<5	<20	50	0.09	<10	50	<10	9	65
2	X14352	1.1	1.17	10	85	<5	1.25	2	12	59	1154	3.36	<10	1.02	410	51	0.04	3	1650	8	<5	<20	85	0.09	<10	54	<10	9	50
3	X14353	1.5	1.21	10	80	<5	1.46	2	12	58	1323	3.10	<10	0.97	421	48	0.03	4	1680	8	<5	<20	58	0.07	<10	38	<10	8	43
4	X14354	1.4	1.16	15	65	<5	1.42	2	10	75	953	3.47	<10	0.96	531	50	0.03	3	1630	28	<5	<20	72	0.07	<10	44	<10	7	92
5	X14355	2.8	1.09	10	50	<5	0.92	3	12	101	2988	3.96	<10	0.91	382	105	0.03	4	1360	50	<5	<20	59	0.06	<10	53	<10	7	62
6	X14356	1.4	1.27	15	50	<5	1.13	3	15	100	1304	4.16	<10	1.13	459	65	0.05	4	1520	10	<5	<20	72	0.08	<10	61	<10	7	68
7	X14357	1.4	1.17	10	65	<5	2.65	3	12	62	1283	3.80	<10	1.04	628	57	0.04	3	1570	10	<5	<20	174	0.07	<10	60	<10	6	61
8	X14358	3.7	1.14	65	55	5	0.76	5	14	58	3229	3.86	20	0.50	265	263	0.03	16	610	120	30	<20	42	0.03	<10	37	<10	8	157
9	X14359	1.3	1.27	10	60	<5	1.78	3	14	71	1196	4.06	<10	1.20	572	90	0.04	3	1440	8	<5	<20	124	0.07	<10	70	<10	7	78
10	X14360	4.7	0.91	15	50	<5	3.16	5	15	70	4440	4.12	<10	0.79	601	147	0.03	3	1200	34	<5	<20	119	0.06	<10	54	<10	7	89
11	X14361	1.2	1.21	15	50	<5	3.36	3	12	49	823	3.74	<10	1.10	707	39	0.04	3	1580	20	<5	<20	286	0.07	<10	58	<10	6	80
12	X14362	1.4	1.27	15	55	<5	2.19	2	11	74	1080	3.59	<10	1.12	569	87	0.04	4	1590	10	<5	<20	157	0.07	<10	59	<10	7	66
13	X14363	1.6	1.39	15	65	<5	1.94	3	14	96	1502	4.07	<10	1.21	680	68	0.04	4	1750	28	<5	<20	107	0.08	<10	64	<10	8	84
14	X14364	1.6	1.20	10	55	<5	2.27	2	11	66	1003	3.42	<10	1.12	494	52	0.04	4	1620	8	<5	<20	238	0.09	<10	62	<10	8	62
15	X14365	0.9	1.21	15	65	<5	0.98	3	12	60	1385	4.31	<10	1.14	518	83	0.04	3	1480	48	<5	<20	110	0.07	<10	69	<10	7	82
16	X14366	1.8	1.40	15	60	<5	1.92	3	14	87	1486	4.11	<10	1.30	759	41	0.05	4	1610	58	<5	<20	116	0.08	<10	69	<10	7	103
17	X14367	1.2	1.31	15	60	<5	1.43	2	12	71	1009	3.74	<10	1.15	642	172	0.03	3	1640	14	<5	<20	67	0.06	<10	50	<10	7	86
18	X14368	1.4	1.33	20	75	<5	2.07	3	13	63	938	4.09	<10	1.23	743	56	0.04	3	1560	14	<5	<20	114	0.07	<10	61	<10	7	86
19	X14369	1.1	1.35	15	50	<5	1.32	3	16	68	1088	4.65	<10	1.24	583	127	0.04	3	1620	26	<5	<20	74	0.07	<10	55	<10	6	77
20	X14370	0.7	1.06	10	110	<5	2.91	3	11	51	759	3.81	<10	0.95	698	42	0.05	3	1640	10	<5	<20	152	0.07	<10	71	<10	6	55
21	X14371	1.1	1.27	15	65	<5	1.91	3	12	84	1063	4.18	<10	1.16	574	37	0.04	3	1560	6	<5	<20	146	0.07	<10	73	<10	6	60
22	X14372	2.6	1.25	15	45	<5	1.73	3	13	85	2317	3.74	<10	1.10	515	74	0.03	4	1310	16	<5	<20	102	0.07	<10	49	<10	7	55
23	X14373	0.8	1.11	10	55	<5	3.22	3	11	65	1041	3.96	<10	1.08	449	55	0.04	3	1410	6	<5	<20	267	0.09	<10	83	<10	7	43
24	X14374	1.4	1.18	15	50	<5	2.94	3	11	73	1789	3.60	<10	1.17	436	83	0.05	4	1520	10	<5	<20	262	0.10	<10	85	<10	8	55
25	X14375	<0.2	0.02	<5	<5	<5	>10	<1	<1	2	2	0.03	<10	1.57	25	<1	<0.01	<1	30	<2	<5	<20	5095	<0.01	<10	1	<10	<1	<1

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X14376	0.8	1.02	10	60	<5	3.44	3	12	69	823	3.83	<10	1.01	520	60	0.05	3	1470	8	<5	<20	271	0.10	<10	97	<10	7	47
27	X14377	1.6	1.19	15	55	<5	3.26	3	11	79	1770	3.61	<10	1.12	527	86	0.04	3	1440	6	<5	<20	254	0.08	<10	76	<10	8	52
28	X14378	1.1	1.08	15	50	<5	3.17	3	10	57	1092	3.46	<10	0.93	461	67	0.03	3	1570	20	<5	<20	240	0.06	<10	63	<10	7	62
29	X14379	0.9	1.16	10	55	<5	2.78	2	10	70	1027	3.02	<10	1.05	525	54	0.05	4	1590	8	<5	<20	217	0.09	<10	84	<10	6	53
30	X14380	0.7	1.00	10	60	<5	2.69	2	10	48	744	3.33	<10	0.92	505	36	0.04	3	1550	8	<5	<20	223	0.08	<10	79	<10	6	42
31	X14381	0.8	1.19	10	50	<5	3.34	3	12	57	706	3.56	<10	1.12	617	40	0.05	3	1560	14	<5	<20	250	0.10	<10	94	<10	6	54
32	X14382	1.3	1.20	10	55	<5	2.58	3	11	75	1137	3.40	<10	1.04	606	41	0.04	3	1510	16	<5	<20	215	0.07	<10	76	<10	7	110
33	X14383	1.6	1.16	10	55	<5	3.50	3	10	56	1667	4.07	<10	1.11	545	32	0.04	3	1490	14	<5	<20	293	0.08	<10	100	<10	7	61
34	X14384	1.5	1.16	15	50	<5	3.29	3	13	62	1191	3.84	<10	1.05	666	32	0.04	3	1520	20	<5	<20	268	0.07	<10	81	<10	7	124
35	X14385	2.0	1.19	15	50	<5	2.88	7	11	73	1366	3.68	<10	1.04	690	57	0.03	3	1440	130	<5	<20	279	0.07	<10	62	<10	7	368
QC DATA:																													
Repeat:																													
1	X14351	1.4	1.19	15	90	<5	1.13	2	10	70	1377	3.10	<10	0.94	363	43	0.04	4	1590	8	<5	<20	49	0.09	<10	48	<10	9	54
10	X14360	4.7	0.92	10	45	<5	3.28	5	15	72	4572	4.22	<10	0.80	615	129	0.03	3	1230	34	<5	<20	124	0.06	<10	56	<10	8	92
19	X14369	1.1	1.32	15	50	<5	1.31	3	16	67	1075	4.57	<10	1.19	579	116	0.03	3	1610	28	<5	<20	72	0.07	<10	53	10	6	76
Resplit:																													
1	X14351	1.3	1.16	15	80	<5	1.05	2	11	72	1247	3.18	<10	0.90	360	46	0.04	4	1670	6	<5	<20	39	0.09	<10	49	<10	9	58
Standard:																													
Pb113A		11.6	0.26	45	60	<5	1.78	39	2	<1	2263	1.03	<10	0.11	1455	60	0.02	<1	100	5648	<5	<20	80	0.01	<10	6	<10	1	6953

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/5711
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5715

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

30-Nov-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07216
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10532	0.27	0.008
2	X10533	0.22	0.006
3	X10534	0.36	0.010
4	X10535	0.17	0.005
5	X10536	0.15	0.004
6	X10537	0.82	0.024
7	X10538	0.27	0.008
8	X10539	0.24	0.007
9	X10540	0.35	0.010
10	X10541	0.81	0.024
11	X10542	1.11	0.032
12	X10543	0.76	0.022
13	X10544	0.94	0.027
14	X10545	1.37	0.040
15	X10546	1.81	0.053
16	X10547	0.94	0.027
17	X10548	1.27	0.037
18	X10549	1.02	0.030
19	X10550	1.19	0.035
20	X10551	0.54	0.016
21	X10552	0.87	0.025
22	X10553	0.35	0.010
23	X10554	0.36	0.010
24	X10555	0.19	0.006
25	X10556	0.56	0.016
26	X10557	0.47	0.014
27	X10558	0.21	0.006
28	X10559	0.31	0.009
29	X10560	0.23	0.007

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5715 30-Nov-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X10561	1.82	0.053
31	X10562	0.64	0.019
32	X10563	0.35	0.010
33	X10564	<0.03	<0.001
34	X10565	0.32	0.009
35	X10566	0.48	0.014

QC DATA:

Repeat:

1	X10532	0.27	0.008
10	X10541	0.86	0.025
11	X10542	0.98	0.029
15	X10546	2.01	0.059
19	X10550	1.27	0.037

Resplits:

1	X10532	0.30	0.009

Standard:

OXK48		3.49	0.102

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 2007-5715

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07216
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10532	0.8	0.22	<5	65	25	0.09	7	36	177	229	>10	<10	<0.01	30	56	<0.01	12	200	18	30	<20	5	0.02	<10	4	<10	<1	64
2	X10533	0.6	0.19	<5	50	40	0.08	1	30	137	156	7.45	<10	<0.01	20	83	<0.01	<1	240	12	<5	<20	9	0.02	<10	3	<10	<1	12
3	X10534	1.3	0.16	<5	70	35	0.06	5	48	181	487	>10	<10	<0.01	20	57	<0.01	11	140	34	20	<20	9	0.02	<10	2	<10	<1	23
4	X10535	0.5	0.20	<5	40	30	0.07	1	30	139	124	7.06	<10	<0.01	15	52	<0.01	3	210	12	<5	<20	4	0.02	<10	2	<10	<1	8
5	X10536	0.4	0.18	<5	55	40	0.07	3	33	162	160	8.35	<10	<0.01	17	73	<0.01	9	190	10	10	<20	5	0.02	<10	3	<10	<1	8
6	X10537	1.3	0.24	<5	45	15	0.10	1	22	151	252	6.44	<10	<0.01	21	44	<0.01	2	340	12	<5	<20	11	0.02	<10	4	<10	<1	11
7	X10538	0.6	0.18	<5	55	40	0.05	4	37	194	173	8.87	<10	<0.01	21	103	<0.01	11	120	18	15	<20	5	0.02	<10	2	<10	<1	17
8	X10539	2.1	0.21	50	40	<5	0.08	3	26	141	616	5.84	<10	<0.01	18	64	<0.01	5	190	14	60	<20	7	0.02	<10	3	<10	<1	38
9	X10540	2.6	0.24	<5	40	<5	0.18	1	22	197	1447	5.62	<10	<0.01	43	28	<0.01	4	370	26	15	<20	19	<0.01	<10	4	<10	<1	15
10	X10541	1.5	0.16	<5	55	20	0.07	2	55	109	372	8.82	<10	<0.01	17	198	<0.01	2	180	24	<5	<20	9	0.03	<10	3	<10	<1	10
11	X10542	2.3	0.20	<5	65	30	0.09	3	67	152	415	>10	<10	<0.01	21	82	<0.01	6	250	20	<5	<20	10	0.03	<10	4	<10	<1	8
12	X10543	1.3	0.22	<5	85	<5	0.08	7	87	144	477	>10	<10	<0.01	20	83	0.01	17	180	20	40	<20	8	0.02	<10	5	<10	<1	7
13	X10544	2.4	0.21	<5	55	<5	0.12	2	48	147	1385	9.31	<10	<0.01	21	281	<0.01	3	280	22	5	<20	6	0.02	<10	4	<10	<1	12
14	X10545	2.0	0.18	<5	90	<5	0.07	5	83	123	1373	>10	<10	<0.01	19	124	<0.01	13	90	26	35	<20	10	0.03	<10	4	<10	<1	14
15	X10546	7.0	0.17	<5	85	<5	0.09	5	68	117	4924	>10	<10	<0.01	18	145	<0.01	6	<10	48	70	<20	19	0.02	<10	6	<10	<1	33
16	X10547	10.3	0.20	30	60	<5	0.10	3	51	187	7829	8.35	<10	<0.01	34	143	<0.01	4	140	50	65	<20	29	0.02	<10	4	<10	<1	37
17	X10548	22.5	0.21	80	50	<5	0.08	6	46	202	9062	7.67	<10	<0.01	33	161	<0.01	4	<10	74	225	<20	26	0.01	<10	4	<10	<1	90
18	X10549	14.8	0.19	30	50	<5	0.09	4	42	164	7773	6.29	<10	<0.01	21	103	<0.01	4	70	62	125	<20	16	<0.01	<10	4	<10	<1	46
19	X10550	10.2	0.18	<5	70	<5	0.12	6	50	148	5516	8.56	<10	<0.01	24	235	<0.01	11	270	58	90	<20	31	<0.01	<10	3	<10	<1	25
20	X10551	11.7	0.19	<5	85	<5	0.10	4	108	161	4221	>10	10	<0.01	23	240	0.01	2	270	38	105	<20	33	0.03	<10	2	<10	<1	44
21	X10552	10.0	0.21	<5	70	<5	0.17	4	65	145	3640	9.03	<10	<0.01	93	115	<0.01	2	240	36	95	<20	38	0.02	<10	3	<10	<1	40
22	X10553	12.4	0.19	85	50	<5	0.29	11	44	128	2794	6.44	10	0.05	151	168	<0.01	23	350	4	260	<20	32	<0.01	<10	8	<10	<1	55
23	X10554	6.4	0.20	10	45	<5	0.16	3	28	173	2739	5.60	<10	<0.01	61	275	<0.01	6	350	28	75	<20	23	<0.01	<10	2	<10	<1	24
24	X10555	3.4	0.22	<5	50	<5	0.24	<1	23	120	2020	5.84	<10	<0.01	108	42	<0.01	<1	560	16	10	<20	22	0.01	<10	2	<10	<1	16
25	X10556	1.7	0.18	<5	90	25	0.06	5	85	119	581	>10	10	<0.01	16	102	<0.01	7	190	20	15	<20	22	0.03	<10	2	<10	<1	13

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10557	1.5	0.18	<5	85	20	0.05	6	68	193	484	>10	10	<0.01	23	72	<0.01	17	160	20	40	<20	7	0.02	<10	2	<10	<1	10
27	X10558	3.6	0.25	<5	40	<5	0.26	<1	16	148	3046	4.96	<10	<0.01	89	17	<0.01	1	580	26	<5	<20	27	0.02	<10	4	<10	<1	13
28	X10559	3.5	0.20	<5	50	<5	0.31	3	15	261	3740	5.19	<10	<0.01	155	12	0.01	10	300	28	50	<20	36	<0.01	<10	4	<10	<1	18
29	X10560	1.8	0.20	<5	35	<5	0.90	6	12	158	3277	3.55	<10	0.03	269	15	0.01	3	510	14	<5	<20	64	0.03	<10	4	<10	<1	547
30	X10561	3.9	1.06	15	55	<5	0.97	4	21	8593	8523	4.02	20	0.59	188	632	0.04	65	130	68	50	<20	55	<0.01	<10	42	<10	7	74
31	X10562	2.2	0.23	<5	35	<5	0.79	5	15	216	4396	4.84	<10	0.12	398	15	<0.01	8	490	14	10	<20	36	<0.01	<10	5	<10	<1	263
32	X10563	1.7	0.23	<5	35	<5	1.03	5	14	138	3251	4.51	<10	0.12	507	19	<0.01	10	670	22	30	<20	43	<0.01	<10	3	<10	<1	137
33	X10564	<0.2	0.03	20	<5	10	>10	<1	2	3	9	0.03	<10	1.73	18	<1	0.01	<1	30	12	<5	<20	6265	0.02	<10	5	<10	<1	<1
34	X10565	4.8	0.20	<5	40	<5	1.05	3	14	147	3027	4.89	<10	<0.01	197	13	<0.01	5	500	20	30	<20	85	<0.01	<10	4	<10	<1	104
35	X10566	2.1	0.20	<5	45	<5	2.18	<1	11	173	3126	4.57	<10	<0.01	408	4	0.01	<1	530	32	<5	<20	172	<0.01	<10	6	<10	<1	93
QC DATA:																													
Repeat:																													
1	X10532	0.6	0.22	<5	65	30	0.08	6	35	177	218	>10	<10	<0.01	30	52	<0.01	11	200	18	25	<20	6	0.02	<10	4	<10	<1	61
10	X10541	1.6	0.17	<5	50	25	0.06	1	53	112	389	8.44	<10	<0.01	14	196	<0.01	2	190	22	<5	<20	7	0.02	<10	3	<10	<1	10
19	X10550	10.8	0.20	<5	70	<5	0.13	6	52	155	5628	8.97	10	<0.01	24	246	<0.01	12	270	62	95	<20	30	<0.01	<10	3	<10	<1	27
Resplit:																													
1	X10532	0.8	0.21	<5	75	30	0.07	8	34	190	225	>10	<10	<0.01	33	50	0.01	10	210	18	35	<20	5	0.03	<10	4	<10	<1	58
Standard:																													
PB113A		11.7	0.25	30	60	<5	1.65	38	2	6	2223	1.00	<10	0.09	1406	66	0.02	2	90	5540	20	<20	89	<0.01	<10	7	<10	<1	6923

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5698S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5716

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

5-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07235
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X14316	0.37	0.011
2	X14317	0.40	0.012
3	X14318	0.29	0.008
4	X14319	0.66	0.019
5	X14320	0.41	0.012
6	X14321	0.45	0.013
7	X14322	0.25	0.007
8	X14323	0.37	0.011
9	X14324	0.48	0.014
10	X14325	0.35	0.010
11	X14326	<0.03	<0.001
12	X14327	0.35	0.010
13	X14328	0.62	0.018
14	X14329	0.42	0.012
15	X14330	0.72	0.021
16	X14331	0.59	0.017
17	X14332	0.48	0.014
18	X14333	0.33	0.010
19	X14334	0.43	0.013
20	X14335	0.51	0.015
21	X14336	0.34	0.010
22	X14337	0.57	0.017
23	X14338	0.46	0.013
24	X14339	0.52	0.015
25	X14340	0.56	0.016
26	X14341	0.28	0.008
27	X14342	0.35	0.010
28	X14343	0.63	0.018

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS2007-5716 5-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	X14344	0.43	0.013
30	X14345	0.63	0.018
31	X14346	0.64	0.019
32	X14347	0.34	0.010
33	X14348	0.32	0.009
34	X14349	0.07	0.002
35	X14350	0.65	0.019

QC DATA:

Repeat:

1	X14316	0.36	0.010
10	X14325	0.34	0.010
19	X14334	0.42	0.012

Resplits:

1	X14316	0.36	0.010

Standard:

SN26		8.60	0.251

AU: 30g FA/AA-Finish

JJ/kk
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5716

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07235
Submitted by: Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X14316	1.0	1.39	<5	90	<5	1.56	1	16	66	979	4.54	<10	1.31	720	78	0.03	6	1510	36	15	<20	61	0.06	<10	68	<10	5	81
2	X14317	1.4	1.35	<5	90	<5	3.38	<1	14	65	1092	4.00	<10	1.26	947	84	0.03	5	1310	34	15	<20	80	0.05	<10	64	<10	6	69
3	X14318	0.9	1.25	<5	70	<5	1.45	8	14	55	781	4.04	<10	1.15	546	131	0.03	5	1460	74	15	<20	57	0.05	<10	61	<10	5	180
4	X14319	1.5	1.34	<5	80	<5	0.87	3	16	82	1492	4.00	<10	1.26	509	76	0.04	7	1470	36	30	<20	44	0.05	<10	69	<10	6	69
5	X14320	1.2	1.37	<5	95	<5	1.76	2	16	53	1259	4.30	<10	1.26	673	61	0.03	5	1550	34	20	<20	56	0.05	<10	62	<10	5	85
6	X14321	1.9	1.21	<5	70	<5	1.01	1	15	50	1181	4.08	<10	1.09	548	90	0.03	5	1720	52	10	<20	37	0.05	<10	57	<10	5	117
7	X14322	2.1	1.15	5	65	<5	1.73	2	13	47	916	3.41	<10	0.96	879	51	0.02	4	1700	42	5	<20	50	0.05	<10	38	<10	5	230
8	X14323	1.5	1.28	<5	115	<5	1.06	1	15	45	1098	3.94	<10	1.21	587	64	0.04	5	1500	36	15	<20	47	0.06	<10	59	<10	4	69
9	X14324	1.2	1.36	<5	85	<5	1.42	2	14	53	1033	4.18	<10	1.28	581	64	0.05	5	1550	36	10	<20	42	0.06	<10	67	<10	4	68
10	X14325	1.3	1.31	<5	100	<5	0.91	3	15	52	927	4.08	<10	1.22	557	84	0.04	9	1670	44	25	<20	50	0.05	<10	67	<10	6	98
11	X14326	<0.2	0.02	15	<5	<5	>10	<1	1	2	2	0.03	<10	2.14	42	<1	<0.01	<1	60	6	15	<20	6719	0.01	<10	2	<10	<1	<1
12	X14327	1.0	1.31	<5	115	<5	0.63	1	15	53	868	3.68	<10	1.25	535	97	0.04	5	1590	38	15	<20	37	0.07	<10	72	<10	5	85
13	X14328	1.3	1.34	<5	95	<5	1.49	2	13	63	1183	3.81	<10	1.27	579	74	0.04	5	1420	36	10	<20	29	0.06	<10	82	<10	4	83
14	X14329	1.4	1.37	<5	65	<5	1.05	20	16	57	1203	4.14	<10	1.31	561	70	0.04	5	1540	48	10	<20	37	0.06	<10	74	<10	5	1181
15	X14330	1.8	1.37	<5	100	<5	0.70	7	14	67	1449	4.28	<10	1.36	459	76	0.04	18	1450	34	75	<20	31	0.01	<10	87	<10	5	83
16	X14331	1.9	1.16	<5	30	<5	1.17	1	13	46	1592	3.46	<10	1.11	409	72	0.02	5	1230	36	10	<20	27	0.08	<10	56	<10	2	64
17	X14332	1.3	1.33	<5	155	<5	1.44	1	13	53	1294	4.10	<10	1.20	476	99	0.03	5	1500	38	10	<20	64	0.05	<10	60	<10	5	79
18	X14333	1.5	1.33	<5	100	<5	0.77	8	14	51	819	4.03	<10	1.21	490	69	0.04	5	1620	42	10	<20	44	0.06	<10	59	<10	7	333
19	X14334	1.6	1.24	<5	80	<5	0.87	3	15	62	1203	3.88	<10	1.06	495	109	0.04	6	1560	44	10	<20	48	0.06	<10	55	<10	5	130
20	X14335	2.0	1.10	<5	65	<5	0.70	1	17	63	1745	3.63	<10	0.99	336	142	0.04	4	1320	36	10	<20	37	0.05	<10	65	<10	4	55
21	X14336	1.4	1.25	<5	60	<5	1.00	8	16	75	1098	4.32	<10	1.20	343	95	0.04	16	1470	38	65	<20	48	0.03	<10	69	<10	3	121
22	X14337	1.6	1.13	<5	15	<5	2.56	1	16	41	1264	3.79	<10	1.06	374	62	0.03	4	1270	32	10	<20	214	0.12	<10	59	<10	<1	54
23	X14338	1.2	1.29	<5	65	<5	2.43	2	17	41	1081	3.97	<10	1.20	406	74	0.03	6	1570	36	15	<20	239	0.08	<10	63	<10	5	63
24	X14339	2.8	1.08	<5	60	<5	2.75	7	16	53	1537	4.11	<10	0.96	496	104	0.02	14	1380	58	65	<20	211	0.02	<10	57	<10	4	167
25	X14340	6.4	0.76	<5	20	<5	2.71	6	16	50	2946	4.18	<10	0.62	634	65	0.02	3	1120	146	<5	<20	188	0.09	<10	30	<10	<1	321

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X14341	2.0	1.19	<5	20	<5	2.68	4	15	39	1035	3.82	<10	1.13	931	59	0.02	5	1280	52	10	<20	181	0.09	<10	53	<10	<1	235
27	X14342	1.3	1.36	<5	175	<5	1.31	1	14	52	729	3.73	<10	1.21	885	54	0.04	6	1670	40	15	<20	77	0.07	<10	66	<10	3	116
28	X14343	2.3	1.20	<5	65	<5	0.79	2	19	76	2085	4.68	<10	1.06	436	167	0.04	7	1260	40	10	<20	40	0.06	<10	71	<10	3	58
29	X14344	1.1	1.19	<5	90	<5	1.56	1	12	54	905	3.54	<10	1.02	540	52	0.03	4	1590	28	5	<20	51	0.05	<10	49	<10	3	59
30	X14345	1.4	1.25	<5	80	<5	1.02	1	22	52	1273	4.05	<10	1.21	411	59	0.04	5	1510	38	10	<20	61	0.05	<10	66	<10	5	47
31	X14346	1.6	1.14	<5	80	<5	1.28	2	18	60	1655	4.26	<10	1.07	446	93	0.04	6	1360	28	15	<20	59	0.05	<10	67	<10	3	48
32	X14347	1.2	1.16	<5	130	<5	1.66	1	14	53	927	3.62	<10	1.01	571	66	0.04	5	1550	32	10	<20	80	0.05	<10	52	<10	6	55
33	X14348	1.2	1.01	5	70	<5	2.02	<1	11	43	711	3.01	<10	0.80	674	47	0.02	<1	1660	54	<5	<20	71	0.04	<10	41	<10	5	90
34	X14349	0.3	0.93	65	145	10	0.31	5	56	227	445	>10	<10	0.19	479	113	0.06	405	130	136	5	<20	21	0.06	<10	25	<10	<1	397
35	X14350	1.7	1.10	<5	75	<5	1.22	2	14	67	1555	3.75	<10	0.97	417	50	0.04	5	1370	36	<5	<20	53	0.06	<10	54	<10	4	45
QC DATA:																													
Repeat:																													
1	X14316	0.9	1.40	<5	95	<5	1.55	2	15	66	968	4.48	<10	1.30	710	79	0.03	4	1470	34	15	<20	71	0.07	<10	68	<10	4	79
10	X14325	1.1	1.35	<5	110	<5	0.91	2	15	52	942	4.05	<10	1.23	555	78	0.05	5	1640	40	20	<20	49	0.06	<10	68	<10	5	96
19	X14334	1.6	1.25	<5	85	<5	0.89	2	15	64	1182	3.87	<10	1.05	491	108	0.04	5	1590	44	10	<20	52	0.07	<10	56	<10	6	132
Resplit:																													
1	X14316	0.8	1.48	<5	100	<5	1.46	2	15	65	891	4.45	<10	1.37	723	78	0.04	7	1530	38	20	<20	59	0.06	<10	71	<10	6	81
Standard:																													
PB113A		11.8	0.27	50	65	<5	1.68	38	2	6	2280	1.05	<10	0.12	1417	62	0.02	4	90	5596	35	<20	81	<0.01	<10	8	<10	<1	6906

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
dl/5680S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5717

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

5-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07213
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10427	0.74	0.022
2	X10428	0.79	0.023
3	X10429	1.27	0.037
4	X10430	1.01	0.029
5	X10431	1.01	0.029
6	X10432	0.65	0.019
7	X10433	1.62	0.047
8	X10434	0.64	0.019
9	X10435	0.45	0.013
10	X10436	0.45	0.013
11	X10437	0.51	0.015
12	X10438	0.27	0.008
13	X10439	0.40	0.012
14	X10440	0.40	0.012
15	X10441	0.49	0.014
16	X10442	0.55	0.016
17	X10443	0.32	0.009
18	X10444	0.37	0.011
19	X10445	0.36	0.010
20	X10446	0.86	0.025
21	X10447	0.81	0.024
22	X10448	0.94	0.027
23	X10449	0.73	0.021
24	X10450	1.47	0.043
25	X10451	0.98	0.029
26	X10452	0.69	0.020
27	X10453	0.80	0.023
28	X10454	1.01	0.029

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS2007-5717 5-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	X10455	0.77	0.022
30	X10456	0.85	0.025
31	X10457	<0.03	<0.001
32	X10458	0.89	0.026
33	X10459	0.32	0.009
34	X10460	0.82	0.024
35	X10461	0.80	0.023

QC DATA:

Repeat:

1	X10427	0.68	0.020
10	X10436	0.44	0.013
19	X10445	0.36	0.010

Resplits:

1	X10427	0.80	0.023

Standard:

SN26		8.57	0.250

AU: 30g FA/AA-Finish

JJ/kk
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5717

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07213
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10427	3.4	1.35	<5	40	<5	1.85	2	15	129	2435	5.53	<10	1.49	1049	12	0.01	6	1000	34	20	<20	172	0.03	<10	69	<10	1	59
2	X10428	3.2	1.23	<5	50	<5	1.70	1	12	100	2532	4.47	<10	1.48	1141	12	0.01	6	920	30	15	<20	136	0.02	<10	60	<10	3	53
3	X10429	3.6	1.44	<5	55	<5	1.66	2	13	102	3391	5.15	<10	1.31	754	10	0.02	6	950	34	10	<20	173	0.02	<10	92	<10	3	52
4	X10430	3.9	1.19	<5	65	<5	1.98	2	16	99	3682	5.50	<10	1.01	690	12	0.01	5	910	36	15	<20	222	0.03	<10	68	<10	4	50
5	X10431	2.4	1.19	<5	50	<5	2.19	1	13	100	1783	4.80	<10	1.01	786	10	0.01	6	940	32	10	<20	232	0.02	<10	64	<10	3	59
6	X10432	2.9	1.16	<5	55	<5	1.59	1	16	92	2029	5.89	<10	1.11	896	12	0.01	6	780	32	10	<20	155	0.03	<10	78	<10	2	55
7	X10433	4.2	1.59	<5	65	<5	2.05	2	16	101	3093	5.70	<10	1.78	1305	12	0.01	7	850	38	20	<20	177	0.03	<10	94	<10	4	56
8	X10434	3.0	1.09	<5	50	<5	1.52	1	13	96	1999	4.84	<10	1.11	1000	12	0.01	6	950	32	10	<20	164	0.03	<10	47	<10	4	51
9	X10435	2.1	1.26	5	40	<5	1.35	2	13	117	1264	5.14	<10	1.21	847	10	0.01	6	860	32	10	<20	109	0.03	<10	52	<10	3	42
10	X10436	2.2	1.15	<5	50	<5	0.84	2	14	111	1105	6.11	<10	0.91	477	14	0.01	6	800	36	10	<20	85	0.03	<10	62	<10	2	29
11	X10437	1.5	1.39	20	45	<5	1.79	3	12	112	1031	5.72	<10	1.34	876	17	0.01	10	840	34	30	<20	147	0.02	<10	66	<10	3	34
12	X10438	1.4	1.48	<5	55	<5	1.27	1	13	85	1259	4.92	<10	1.35	677	12	0.01	5	930	38	15	<20	125	0.02	<10	53	<10	4	57
13	X10439	1.4	1.46	<5	55	<5	4.66	1	13	78	1049	5.08	<10	1.77	1924	11	0.02	4	920	38	20	<20	310	0.04	<10	53	<10	8	52
14	X10440	1.5	1.44	15	55	<5	1.83	<1	12	84	1108	4.68	<10	1.29	787	12	0.02	5	970	34	10	<20	141	0.02	<10	57	<10	6	52
15	X10441	2.2	1.13	10	45	<5	1.70	1	12	108	1673	5.02	<10	1.03	688	11	0.01	7	890	32	10	<20	149	0.02	<10	44	<10	4	43
16	X10442	2.3	1.30	10	60	<5	2.14	1	13	73	1935	4.75	<10	1.10	726	12	0.01	5	1080	34	15	<20	224	0.02	<10	60	<10	4	49
17	X10443	1.7	1.03	10	55	<5	2.00	<1	11	103	1244	4.13	<10	0.92	747	12	0.02	5	1050	32	10	<20	210	0.02	<10	45	<10	3	37
18	X10444	1.9	1.03	<5	50	<5	2.01	1	13	86	1603	4.64	<10	0.89	719	10	0.01	3	760	30	<5	<20	188	0.02	<10	42	<10	3	41
19	X10445	1.9	1.40	10	65	<5	3.33	2	13	107	1436	4.99	<10	1.23	1177	11	0.01	7	1020	36	15	<20	260	0.03	<10	54	<10	7	54
20	X10446	2.5	0.89	30	45	<5	2.85	2	17	57	1531	3.75	<10	0.73	1405	43	<0.01	4	1350	62	5	<20	69	0.02	<10	20	<10	3	117
21	X10447	2.7	1.24	30	50	<5	1.02	2	18	62	1779	4.38	<10	0.96	823	45	<0.01	5	1450	56	10	<20	48	0.02	<10	25	<10	1	131
22	X10448	3.4	1.13	10	35	<5	0.87	3	17	73	2323	4.43	<10	0.96	938	41	0.01	9	1260	98	30	<20	38	0.01	<10	27	<10	2	119
23	X10449	3.4	0.96	15	50	<5	0.66	2	17	106	2364	3.98	<10	0.72	706	32	<0.01	6	1220	46	10	<20	42	0.02	<10	20	<10	2	86
24	X10450	4.8	0.65	5	45	<5	1.13	2	15	96	3607	4.61	<10	0.48	795	24	<0.01	6	990	50	5	<20	44	0.02	<10	15	<10	1	62
25	X10451	2.6	1.02	10	75	<5	1.37	1	11	83	1904	3.65	<10	0.74	904	21	0.02	6	1420	48	10	<20	64	0.02	<10	32	<10	3	82

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10452	2.9	0.81	<5	45	<5	0.92	1	11	103	2118	3.24	<10	0.61	733	25	0.02	5	1040	48	10	<20	45	0.02	<10	21	<10	2	72
27	X10453	1.6	0.82	15	60	<5	0.75	<1	11	70	1017	3.87	<10	0.46	425	14	0.02	4	1530	28	<5	<20	53	0.02	<10	32	<10	3	56
28	X10454	4.8	0.51	<5	45	<5	0.78	2	15	98	3759	4.52	<10	0.29	499	26	0.01	5	1020	62	<5	<20	48	0.02	<10	18	<10	<1	43
29	X10455	4.2	0.72	5	55	<5	0.46	2	20	121	2764	4.74	<10	0.50	458	22	0.02	8	880	88	10	<20	45	0.02	<10	23	<10	2	76
30	X10456	2.7	0.87	10	60	<5	0.75	3	14	67	1765	3.70	<10	0.62	625	37	0.01	7	1500	70	25	<20	40	<0.01	<10	27	<10	4	133
31	X10457	<0.2	0.02	25	<5	<5	>10	<1	2	4	6	0.04	<10	1.75	33	<1	<0.01	<1	50	10	10	<20	6464	<0.01	<10	4	<10	<1	<1
32	X10458	2.5	0.93	10	70	<5	1.64	1	14	64	1464	3.90	<10	0.72	1164	43	0.04	7	1540	42	10	<20	70	0.03	<10	44	<10	3	88
33	X10459	3.2	1.11	35	55	<5	0.98	3	21	55	2593	3.51	10	0.63	199	200	0.04	11	510	74	30	<20	59	0.03	<10	48	<10	5	272
34	X10460	3.0	0.87	5	40	<5	0.96	1	13	53	2172	3.89	<10	0.66	704	28	0.01	5	1460	42	<5	<20	44	0.02	<10	29	<10	2	66
35	X10461	2.8	0.96	10	60	<5	0.98	<1	15	115	1899	4.14	<10	0.66	610	30	0.03	6	1310	46	<5	<20	55	0.02	<10	36	<10	3	62
QC DATA:																													
Repeat:																													
1	X10427	3.2	1.33	<5	45	<5	1.80	1	15	131	2325	5.37	<10	1.44	1017	11	0.01	8	990	38	15	<20	187	0.03	<10	69	<10	4	57
10	X10436	2.2	1.11	5	50	<5	0.80	1	14	108	1048	5.85	<10	0.86	455	14	0.01	6	780	36	10	<20	84	0.03	<10	60	<10	1	29
19	X10445	2.0	1.43	5	65	<5	3.34	1	13	110	1463	5.01	<10	1.25	1192	11	0.01	6	1000	34	15	<20	258	0.03	<10	56	<10	6	53
Resplit:																													
1	X10427	3.1	1.34	5	50	<5	1.78	2	15	130	2455	5.58	<10	1.45	1036	11	0.01	10	1070	38	20	<20	169	0.03	<10	72	<10	3	61
Standard:																													
Pb113A		11.8	0.25	50	55	<5	1.66	36	3	7	2154	1.04	<10	0.11	1504	60	0.02	3	90	5420	20	<20	80	<0.01	<10	11	<10	<1	6983

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
dl/5680S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5718

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

3-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07219
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10637	1.13	0.033
2	X10638	1.09	0.032
3	X10639	1.25	0.036
4	X10640	1.74	0.051
5	X10641	2.53	0.074
6	X10642	1.42	0.041
7	X10643	1.58	0.046
8	X10644	0.91	0.027
9	X10645	1.62	0.047
10	X10646	1.92	0.056
11	X10647	1.96	0.057
12	X10648	0.51	0.015
13	X10649	1.47	0.043
14	X10650	1.04	0.030
15	X10651	1.08	0.031
16	X10652	1.12	0.033
17	X10653	1.69	0.049
18	X10654	2.19	0.064
19	X10655	3.60	0.105
20	X10656	1.37	0.040
21	X10657	1.42	0.041
22	X10658	1.04	0.030
23	X10659	1.31	0.038
24	X10660	0.94	0.027
25	X10661	1.16	0.034
26	X10662	1.30	0.038
27	X10663	1.12	0.033
28	X10664	0.87	0.025
29	X10665	0.66	0.019

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS-5718 3-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X10666	0.80	0.023
31	X10667	1.13	0.033
32	X10668	0.89	0.026
33	X10669	<0.03	<0.001
34	X10670	0.34	0.010
35	X10671	1.01	0.029

QC DATA:

Repeat:

1	X10637	1.07	0.031
5	X10641	2.39	0.070
9	X10645	1.52	0.044
10	X10646	2.08	0.061
11	X10647	1.86	0.054
19	X10655	3.40	0.099
28	X10664	0.78	0.023
31	X10667	1.09	0.032

Resplits:

1	X10637	1.08	0.031

Standard:

OXK48		3.58	0.104

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5718

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07219
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10637	2.4	0.60	10	40	<5	1.24	3	5	84	2985	3.73	<10	0.58	864	8	0.01	<1	710	84	<5	<20	43	<0.01	<10	8	<10	2	131
2	X10638	3.2	0.35	5	35	<5	0.66	3	8	104	3746	4.09	<10	0.22	429	11	0.01	<1	670	68	<5	<20	24	<0.01	<10	6	<10	2	66
3	X10639	2.3	0.45	5	40	<5	0.73	3	8	96	2828	4.13	<10	0.32	450	11	0.01	<1	780	26	<5	<20	23	<0.01	<10	8	<10	2	38
4	X10640	3.3	0.46	5	45	<5	0.49	4	13	119	4557	5.75	<10	0.26	309	10	0.02	<1	730	58	<5	<20	23	<0.01	<10	9	<10	1	52
5	X10641	4.5	0.74	10	50	<5	0.42	4	13	97	6155	5.75	<10	0.55	521	10	0.01	<1	690	80	<5	<20	16	<0.01	<10	14	<10	1	81
6	X10642	2.1	1.15	15	60	<5	0.60	3	9	96	2906	4.32	<10	0.86	584	11	0.01	<1	970	46	<5	<20	22	<0.01	<10	15	<10	2	73
7	X10643	2.4	0.92	10	55	<5	1.21	3	7	89	2901	4.18	<10	0.71	592	10	0.01	<1	820	46	<5	<20	76	<0.01	<10	14	<10	3	76
8	X10644	3.5	0.21	10	45	<5	0.44	4	13	123	4182	5.40	<10	0.03	218	8	0.01	<1	510	114	<5	<20	29	<0.01	<10	5	<10	<1	34
9	X10645	4.1	0.44	10	45	<5	0.66	5	10	133	4905	4.36	<10	0.22	449	16	0.01	<1	600	162	<5	<20	32	<0.01	<10	8	<10	2	130
10	X10646	4.2	0.68	15	45	<5	0.56	3	8	135	3958	4.48	<10	0.38	455	12	0.01	<1	740	110	<5	<20	32	<0.01	<10	10	<10	2	98
11	X10647	8.5	0.57	20	50	<5	1.19	4	10	113	5925	4.65	<10	0.37	653	19	0.01	<1	790	80	<5	<20	84	<0.01	<10	7	<10	2	115
12	X10648	4.8	0.23	20	45	<5	1.47	17	14	126	3299	5.39	<10	0.10	752	40	0.02	<1	620	106	10	<20	87	<0.01	<10	6	<10	4	1125
13	X10649	4.4	0.91	15	50	<5	1.01	6	7	109	4877	4.75	<10	0.64	692	6	0.01	<1	650	130	<5	<20	73	<0.01	<10	20	<10	2	296
14	X10650	3.8	0.21	25	40	<5	0.94	3	7	115	2717	3.90	<10	0.21	620	8	0.01	<1	720	52	<5	<20	43	<0.01	<10	4	<10	3	40
15	X10651	2.8	0.88	40	45	<5	0.57	3	6	98	2405	4.28	<10	0.65	550	9	0.01	<1	760	36	<5	<20	33	<0.01	<10	12	<10	2	86
16	X10652	3.0	0.96	20	50	<5	0.72	3	8	111	2374	4.37	<10	0.69	600	16	0.01	<1	750	40	<5	<20	43	<0.01	<10	12	<10	2	65
17	X10653	6.1	0.49	65	50	<5	0.59	4	11	111	4507	6.30	<10	0.33	534	23	0.02	<1	780	28	<5	<20	29	<0.01	<10	8	<10	2	52
18	X10654	4.3	0.34	40	40	<5	0.31	4	9	134	3632	4.83	<10	0.15	281	18	0.02	<1	770	70	<5	<20	19	<0.01	<10	7	<10	2	44
19	X10655	3.4	0.50	45	40	<5	0.30	3	7	105	2687	4.59	<10	0.31	451	17	0.01	<1	630	34	<5	<20	18	<0.01	<10	10	<10	2	51
20	X10656	3.0	0.61	15	40	<5	0.51	3	11	99	2992	4.72	<10	0.47	565	24	0.02	<1	830	30	<5	<20	34	<0.01	<10	12	<10	2	71
21	X10657	3.3	0.57	5	45	<5	0.87	4	10	103	2612	5.08	<10	0.42	584	13	0.02	<1	710	62	<5	<20	39	<0.01	<10	12	<10	2	105
22	X10658	5.0	0.44	15	40	<5	0.66	4	11	99	2635	5.34	<10	0.23	360	19	0.02	<1	780	58	<5	<20	41	<0.01	<10	10	<10	2	61
23	X10659	4.7	0.46	25	45	<5	1.06	3	12	135	3704	5.13	<10	0.27	650	21	0.02	<1	710	52	<5	<20	55	<0.01	<10	10	<10	3	60
24	X10660	5.5	0.35	5	40	<5	0.33	6	12	120	4874	4.15	<10	0.19	320	38	0.02	<1	570	240	5	<20	34	<0.01	<10	11	<10	1	518
25	X10661	6.3	0.37	15	40	<5	0.41	5	11	146	6870	4.58	<10	0.20	399	32	0.02	<1	500	104	<5	<20	31	<0.01	<10	9	<10	<1	176

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10662	5.7	0.39	10	45	<5	0.43	3	13	118	6333	5.06	<10	0.21	321	37	0.02	<1	590	52	<5	<20	51	<0.01	<10	11	<10	1	41
27	X10663	8.4	0.18	10	45	<5	0.33	7	13	149	8603	4.36	<10	0.03	175	26	0.01	<1	340	228	<5	<20	40	<0.01	<10	5	<10	<1	198
28	X10664	5.1	0.27	5	45	<5	0.59	3	8	146	4614	4.81	<10	0.11	221	21	0.02	<1	490	58	<5	<20	73	<0.01	<10	9	<10	1	26
29	X10665	4.7	0.22	5	40	<5	0.61	3	8	154	4881	4.17	<10	0.07	221	23	0.01	<1	380	60	<5	<20	63	<0.01	<10	6	<10	<1	21
30	X10666	2.5	0.45	25	40	<5	1.10	3	6	134	2368	3.82	<10	0.30	536	12	0.01	1	690	48	<5	<20	61	<0.01	<10	7	<10	2	79
31	X10667	2.9	0.71	15	45	<5	1.01	3	7	115	2543	4.57	<10	0.54	607	10	0.02	<1	760	18	<5	<20	58	<0.01	<10	13	<10	2	77
32	X10668	11.4	0.32	35	40	<5	0.67	5	11	138	4485	4.51	<10	0.15	349	43	0.02	<1	730	74	15	<20	39	<0.01	<10	8	<10	2	84
33	X10669	<0.2	0.04	<5	<5	<5	>10	<1	<1	4	5	0.51	<10	1.56	81	<1	<0.01	<1	30	2	<5	<20	6263	<0.01	<10	3	<10	<1	<1
34	X10670	7.7	0.18	10	40	<5	0.44	4	11	112	4959	5.69	<10	0.02	113	16	0.02	<1	670	60	<5	<20	49	<0.01	<10	6	<10	1	29
35	X10671	3.6	1.05	70	65	10	0.75	5	15	58	3363	3.88	20	0.47	285	217	0.03	16	430	122	30	<20	43	0.03	<10	36	<10	8	177
QC DATA:																													
Repeat:																													
1	X10637	2.8	0.59	10	45	<5	1.29	3	6	85	3044	3.68	<10	0.58	885	9	0.01	<1	720	84	<5	<20	41	<0.01	<10	8	<10	2	133
10	X10646	4.2	0.65	15	45	<5	0.54	3	8	131	3949	4.49	<10	0.38	450	12	0.02	<1	730	108	<5	<20	31	<0.01	<10	10	<10	2	98
19	X10655	3.6	0.48	50	40	<5	0.28	3	8	102	2727	4.70	<10	0.32	455	19	0.01	<1	650	34	5	<20	19	<0.01	<10	10	<10	2	53
Resplit:																													
1	X10637	2.7	0.57	10	45	<5	1.28	4	8	84	3010	4.27	<10	0.50	886	11	0.01	<1	690	80	<5	<20	39	<0.01	<10	8	<10	2	147
Standard:																													
PB113A		11.0	0.24	50	65	<5	1.74	41	2	<1	2252	1.00	<10	0.10	1489	61	0.01	<1	100	5580	<5	<20	80	<0.01	<10	7	<10	1	7106

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/n5718S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5719

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

3-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07215
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10497	0.92	0.027
2	X10498	0.93	0.027
3	X10499	0.73	0.021
4	X10500	<0.03	<0.001
5	X10501	0.73	0.021
6	X10502	0.65	0.019
7	X10503	1.81	0.053
8	X10504	1.03	0.030
9	X10505	0.68	0.020
10	X10506	0.74	0.022
11	X10507	0.99	0.029
12	X10508	0.80	0.023
13	X10509	0.51	0.015
14	X10510	0.47	0.014
15	X10511	1.14	0.033
16	X10512	0.53	0.015
17	X10513	1.02	0.030
18	X10514	0.23	0.007
19	X10515	0.63	0.018
20	X10516	0.54	0.016
21	X10517	0.40	0.012
22	X10518	0.30	0.009
23	X10519	0.38	0.011
24	X10520	0.55	0.016
25	X10521	0.53	0.015
26	X10522	0.15	0.004
27	X10523	0.57	0.017
28	X10524	0.63	0.018
29	X10525	0.15	0.004

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5719 3-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X10526	2.46	0.072
31	X10527	1.23	0.036
32	X10528	0.27	0.008
33	X10529	0.23	0.007
34	X10530	0.31	0.009
35	X10531	0.33	0.010

QC DATA:

Repeat:

1	X10497	0.85	0.025
10	X10506	0.69	0.020
15	X10511	1.16	0.034
19	X10515	0.71	0.021
30	X10526	2.47	0.072

Resplits:

1	X10497	0.92	0.027

Standard:

OXK48		3.58	0.104

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5719

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07215
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10497	2.2	0.93	15	45	<5	1.41	4	9	93	2108	3.87	<10	0.59	608	11	0.02	<1	1080	34	<5	<20	64	<0.01	<10	12	<10	3	151
2	X10498	2.5	1.06	15	45	<5	1.05	3	8	64	2013	4.19	<10	0.75	453	16	0.02	<1	1110	26	<5	<20	53	<0.01	<10	18	<10	4	119
3	X10499	2.1	0.92	10	45	<5	1.50	2	9	75	2029	3.34	<10	0.70	816	14	0.02	<1	1180	36	<5	<20	69	<0.01	<10	14	<10	4	99
4	X10500	<0.2	0.02	<5	<5	<5	>10	<1	<1	1	2	0.05	<10	1.61	36	<1	<0.01	<1	50	<2	<5	<20	6282	<0.01	<10	2	<10	<1	<1
5	X10501	2.2	0.58	15	40	<5	0.51	3	9	60	1905	4.12	<10	0.31	316	21	0.01	<1	1210	34	<5	<20	23	<0.01	<10	8	<10	3	125
6	X10502	2.1	0.89	15	45	<5	0.39	2	9	77	2007	4.43	<10	0.46	316	17	0.01	<1	1120	20	<5	<20	18	<0.01	<10	8	<10	3	111
7	X10503	3.8	0.98	40	60	<5	1.02	4	19	55	8576	4.05	10	0.54	211	597	0.04	66	510	54	25	<20	59	0.04	<10	35	<10	7	78
8	X10504	2.4	0.65	10	40	<5	0.98	2	11	66	2097	3.66	<10	0.41	648	14	0.01	<1	1000	28	<5	<20	45	<0.01	<10	9	<10	3	86
9	X10505	2.1	0.54	10	40	<5	0.73	3	9	107	1823	4.53	<10	0.28	407	11	0.01	<1	1100	42	<5	<20	32	<0.01	<10	8	<10	3	88
10	X10506	2.1	0.39	10	35	<5	0.37	3	10	93	1985	4.23	<10	0.16	195	13	0.01	<1	960	36	<5	<20	18	<0.01	<10	6	<10	2	54
11	X10507	2.4	0.60	20	40	<5	0.41	2	9	89	2042	4.24	<10	0.33	268	11	0.01	<1	1020	18	<5	<20	18	<0.01	<10	7	<10	3	79
12	X10508	2.4	1.03	20	45	<5	0.33	2	7	70	2154	3.27	<10	0.72	318	18	<0.01	<1	1080	8	<5	<20	15	<0.01	<10	9	<10	3	154
13	X10509	3.4	0.29	15	30	<5	0.31	5	10	128	3521	4.29	<10	0.07	184	10	0.01	<1	980	40	<5	<20	16	<0.01	<10	5	<10	2	108
14	X10510	3.5	0.30	10	35	<5	0.36	3	15	90	3700	5.32	<10	0.11	190	10	0.01	<1	800	48	<5	<20	18	<0.01	<10	4	<10	2	60
15	X10511	4.4	0.25	20	45	<5	1.03	4	20	119	4385	5.67	<10	0.14	433	8	0.02	<1	740	44	<5	<20	44	<0.01	<10	4	<10	2	29
16	X10512	4.1	0.20	10	40	<5	0.52	6	16	84	3606	5.92	<10	0.02	141	14	0.02	<1	1020	68	<5	<20	25	<0.01	<10	4	<10	2	155
17	X10513	3.1	0.32	5	40	<5	0.90	3	10	124	2760	4.18	<10	0.23	517	14	0.01	1	990	28	<5	<20	31	<0.01	<10	6	<10	3	54
18	X10514	2.8	0.20	10	45	<5	0.80	5	43	98	2901	6.84	<10	0.06	284	16	0.02	<1	930	46	<5	<20	29	<0.01	<10	3	<10	2	95
19	X10515	2.6	0.22	10	40	<5	1.85	3	8	89	2497	4.63	<10	0.20	482	13	0.01	<1	1040	28	<5	<20	50	<0.01	<10	5	<10	3	82
20	X10516	3.9	0.21	<5	40	<5	0.85	4	9	94	3745	5.77	<10	0.03	258	11	0.01	<1	920	28	<5	<20	26	<0.01	<10	4	<10	2	96
21	X10517	4.3	0.22	5	40	<5	0.81	4	9	96	3827	5.42	<10	0.03	275	8	0.01	<1	1050	26	<5	<20	25	<0.01	<10	4	<10	2	105
22	X10518	4.1	0.22	25	45	<5	1.32	4	17	102	3320	6.82	<10	0.10	573	12	0.02	<1	960	34	15	<20	30	<0.01	<10	3	<10	2	82
23	X10519	3.2	0.22	15	40	<5	1.45	4	11	117	2593	5.19	<10	0.14	622	9	0.01	<1	990	30	5	<20	29	<0.01	<10	4	<10	3	75
24	X10520	4.2	0.19	5	40	<5	1.32	3	14	77	3676	5.23	<10	0.08	485	8	0.01	<1	1040	44	<5	<20	33	<0.01	<10	3	<10	2	56
25	X10521	5.6	0.22	15	40	<5	0.71	5	11	113	4848	6.31	<10	0.05	280	6	0.02	<1	1140	46	10	<20	22	<0.01	<10	3	<10	2	159

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10522	3.2	0.20	35	40	<5	0.28	4	12	105	3748	5.99	<10	0.04	141	8	0.01	<1	860	24	30	<20	14	<0.01	<10	3	<10	<1	44
27	X10523	4.6	0.21	85	45	<5	0.17	5	18	150	3310	8.46	<10	0.02	49	7	0.02	<1	820	30	50	<20	13	<0.01	<10	3	<10	<1	41
28	X10524	3.2	0.20	50	45	5	0.16	4	28	101	1007	8.90	<10	0.01	21	18	0.02	<1	870	16	20	<20	10	<0.01	<10	2	<10	<1	20
29	X10525	1.9	0.15	40	55	<5	0.17	6	55	125	976	>10	<10	0.01	69	45	0.02	<1	740	22	20	<20	10	<0.01	<10	2	10	<1	20
30	X10526	11.5	0.22	210	50	<5	0.41	12	20	107	4767	8.07	<10	0.08	287	11	0.02	<1	990	54	145	<20	14	<0.01	<10	3	<10	<1	395
31	X10527	10.8	0.24	145	40	<5	0.28	6	14	152	4446	6.32	<10	0.05	141	10	0.02	<1	980	34	130	<20	13	<0.01	<10	3	<10	<1	91
32	X10528	3.7	0.20	50	40	<5	0.27	5	18	108	2980	7.08	<10	0.05	151	20	0.02	<1	880	24	40	<20	14	<0.01	<10	3	<10	<1	32
33	X10529	5.9	0.20	100	40	5	0.22	5	14	165	3571	7.24	<10	0.02	117	6	0.02	<1	760	28	120	<20	14	<0.01	<10	3	<10	<1	58
34	X10530	4.6	0.19	80	40	<5	0.36	6	15	109	1853	6.79	<10	0.08	321	19	0.02	<1	680	34	135	<20	15	<0.01	<10	3	<10	<1	66
35	X10531	2.5	0.17	50	45	<5	0.15	4	22	159	1683	8.10	<10	<0.01	64	31	0.02	<1	600	20	50	<20	8	<0.01	<10	3	<10	<1	25
QC DATA:																													
Repeat:																													
1	X10497	2.3	0.94	10	45	<5	1.46	4	9	92	2092	3.90	<10	0.60	616	11	0.02	<1	1100	24	<5	<20	65	<0.01	<10	12	<10	3	140
10	X10506	2.2	0.37	10	35	<5	0.37	3	10	88	1934	4.20	<10	0.16	190	13	0.01	<1	940	38	<5	<20	19	<0.01	<10	6	<10	2	53
19	X10515	2.5	0.21	10	40	<5	1.87	3	8	90	2551	4.76	<10	0.20	506	11	0.01	<1	1070	26	<5	<20	49	<0.01	<10	5	<10	3	87
Resplit:																													
1	X10497	2.3	0.89	10	40	<5	1.41	3	8	84	2036	3.82	<10	0.55	585	14	0.02	<1	1130	22	<5	<20	64	<0.01	<10	11	<10	3	121
Standard:																													
Pb113A		11.9	0.24	50	60	<5	1.71	40	2	2	2281	1.00	<10	0.10	1492	68	0.01	<1	100	5576	5	<20	89	<0.01	<10	6	<10	1	7040

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/n5718S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5720

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07228
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	X12456	0.58	0.017		
2	X12457	0.57	0.017		
3	X12458	0.35	0.010		
4	X12459	0.56	0.016		
5	X12460	0.52	0.015		
6	X12461	0.61	0.018		
7	X12462	0.66	0.019		
8	X12463	0.75	0.022		
9	X12464	0.76	0.022		
10	X12465	1.17	0.034		
11	X12466	0.41	0.012		
12	X12467	0.38	0.011		
13	X12468	0.49	0.014		
14	X12469	0.50	0.015		
15	X12470	0.64	0.019		
16	X12471	0.64	0.019		
17	X12472	0.89	0.026		
18	X12473	0.62	0.018		
19	X12474	0.59	0.017		
20	X12475	0.53	0.015		
21	X12476	0.48	0.014		
22	X12477	1.05	0.031		
23	X12478	<0.03	<0.001		
24	X12479	0.39	0.011		
25	X12480	0.73	0.021		
26	X12481	0.53	0.015	46.1	1.344
27	X12482	0.33	0.010		
28	X12483	0.41	0.012		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS2007-5720 4-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
29	X12484	0.41	0.012		
30	X12485	0.58	0.017	76.8	2.240
31	X12486	0.51	0.015		
32	X12487	0.86	0.025	94.4	2.753
33	X12488	0.84	0.024		
34	X12489	0.66	0.019		
35	X12490	0.31	0.009		
QC DATA:					
Repeat:					
1	X12456	0.57	0.017		
10	X12465	1.08	0.031		
19	X12474	0.52	0.015		
Resplits:					
1	X12456	0.56	0.016		
Standard:					
OXK48		3.57	0.104		
Pb113				22.6	0.659

AU: 30g FA/AA-Finish

JJ/kk
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 2007-5720

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07228
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X12456	2.3	0.83	15	55	<5	0.93	2	8	155	2203	3.74	<10	0.63	618	15	0.02	3	980	26	<5	<20	68	<0.01	<10	15	<10	5	64
2	X12457	2.2	0.80	10	55	<5	1.01	2	8	116	2182	3.66	<10	0.66	658	12	0.03	2	940	26	<5	<20	67	<0.01	<10	15	<10	4	57
3	X12458	1.3	0.80	10	75	<5	1.86	3	7	79	967	4.27	<10	0.61	746	9	0.02	<1	1050	26	<5	<20	134	<0.01	<10	26	<10	4	73
4	X12459	2.2	0.68	15	50	<5	2.37	2	7	81	1962	3.56	<10	0.43	749	14	0.02	<1	1100	24	<5	<20	181	<0.01	<10	14	<10	4	62
5	X12460	1.9	0.82	15	60	<5	1.46	2	9	100	1613	3.79	<10	0.54	516	12	0.02	1	1080	22	<5	<20	73	<0.01	<10	16	<10	4	66
6	X12461	1.8	0.83	15	60	<5	1.52	2	8	104	1581	3.72	<10	0.55	538	14	0.02	1	1080	22	<5	<20	79	<0.01	<10	16	<10	4	66
7	X12462	2.8	0.73	10	50	<5	1.87	3	9	101	2630	4.06	<10	0.51	553	24	0.02	1	1090	20	<5	<20	188	<0.01	<10	17	<10	5	52
8	X12463	2.3	0.54	20	40	<5	1.96	2	8	98	2472	4.30	<10	0.41	560	25	0.02	<1	1060	20	<5	<20	119	<0.01	<10	10	<10	4	36
9	X12464	2.7	0.66	20	45	<5	2.24	3	9	107	2615	4.34	<10	0.62	635	34	0.02	<1	1020	16	<5	<20	326	<0.01	<10	16	<10	4	46
10	X12465	4.9	0.46	20	45	<5	1.64	3	12	124	3935	4.91	<10	0.41	520	38	0.02	<1	810	18	<5	<20	290	<0.01	<10	12	<10	3	38
11	X12466	5.3	0.08	25	35	<5	1.07	2	8	297	2779	2.25	<10	0.13	551	189	<0.01	6	170	30	10	<20	57	<0.01	<10	2	<10	<1	24
12	X12467	4.8	0.09	5	35	<5	0.61	2	10	180	4515	3.53	<10	0.06	274	309	0.01	2	280	36	<5	<20	41	<0.01	<10	3	<10	1	9
13	X12468	2.2	0.92	10	60	<5	2.24	2	7	86	1849	3.98	<10	0.60	1006	24	0.02	1	1050	12	<5	<20	222	<0.01	<10	20	<10	7	68
14	X12469	1.8	0.69	10	70	<5	2.18	2	8	71	1242	3.05	<10	0.42	957	15	0.01	1	1070	10	<5	<20	225	<0.01	<10	14	<10	5	52
15	X12470	2.8	0.83	10	80	<5	1.70	2	8	112	2140	2.95	<10	0.55	783	18	0.01	2	1040	14	<5	<20	157	<0.01	<10	14	<10	5	57
16	X12471	2.9	0.87	35	60	<5	1.53	2	7	77	1909	3.58	<10	0.60	981	11	0.01	2	1060	16	<5	<20	123	<0.01	<10	15	<10	5	66
17	X12472	2.6	0.78	15	75	<5	1.61	2	7	82	2387	3.41	<10	0.55	773	12	0.01	1	1000	16	<5	<20	146	<0.01	<10	16	<10	5	54
18	X12473	2.5	0.74	10	85	<5	2.19	2	7	94	2207	3.01	<10	0.50	932	12	0.02	2	830	12	<5	<20	243	<0.01	<10	14	<10	5	50
19	X12474	2.1	0.80	15	80	<5	2.57	2	8	98	1722	3.60	<10	0.53	987	10	0.01	2	1050	14	<5	<20	245	<0.01	<10	18	<10	5	48
20	X12475	4.8	0.77	40	60	<5	2.82	3	8	94	2031	3.23	<10	0.50	1413	11	0.01	2	1000	38	15	<20	207	<0.01	<10	10	<10	5	78
21	X12476	2.7	0.81	35	50	<5	1.92	2	9	92	1418	3.52	<10	0.62	1257	12	0.01	2	1180	20	<5	<20	137	<0.01	<10	11	<10	5	59
22	X12477	3.6	1.00	65	65	10	0.73	4	15	58	3261	3.87	20	0.46	289	211	0.03	16	630	126	30	<20	37	0.03	<10	35	<10	8	165
23	X12478	<0.2	0.02	<5	<5	<5	>10	<1	<1	2	3	0.02	<10	1.47	21	<1	<0.01	<1	50	2	<5	<20	6491	<0.01	<10	3	<10	<1	<1
24	X12479	1.9	1.10	15	70	<5	1.83	2	9	107	1185	3.83	<10	0.86	1035	9	0.01	2	1060	12	<5	<20	149	<0.01	<10	15	<10	5	72
25	X12480	9.3	0.45	90	40	10	2.13	10	8	75	2328	5.23	<10	0.43	1438	9	0.02	<1	1130	68	5	<20	96	<0.01	<10	8	<10	5	536

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007-5720 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X12481	>30	0.31	275	50	65	1.75	18	8	103	3260	6.19	<10	0.42	1460	8	0.02	<1	1020	158	465	<20	68	<0.01	<10	6	<10	4	1364
27	X12482	10.4	0.24	80	40	5	1.09	11	7	133	2572	4.15	<10	0.21	1050	15	0.01	2	870	200	95	<20	34	<0.01	<10	6	<10	3	888
28	X12483	5.6	0.33	75	45	<5	1.75	5	7	129	1944	4.33	<10	0.51	1775	20	0.01	2	970	100	80	<20	47	<0.01	<10	6	<10	5	279
29	X12484	12.3	0.30	75	40	15	1.19	14	7	107	2498	5.19	<10	0.30	1108	11	0.01	<1	1190	306	55	<20	38	<0.01	<10	6	<10	4	1131
30	X12485	>30	0.19	135	50	30	1.37	20	8	175	4181	8.34	<10	0.07	953	8	0.02	<1	720	330	230	<20	55	<0.01	<10	3	<10	2	1454
31	X12486	23.4	0.30	70	40	<5	1.78	7	8	144	2489	4.17	<10	0.40	1376	12	0.01	2	950	146	40	<20	54	<0.01	<10	5	<10	5	436
32	X12487	>30	0.78	80	45	95	1.39	29	8	111	1890	4.09	<10	0.88	1293	13	0.01	2	960	806	25	<20	58	<0.01	<10	10	<10	5	2688
33	X12488	4.3	1.08	35	55	<5	1.50	2	7	110	2811	3.97	<10	1.08	1137	13	0.01	2	1030	14	<5	<20	93	<0.01	<10	14	<10	5	86
34	X12489	11.8	0.33	30	45	<5	1.73	2	14	156	5473	3.73	<10	0.65	1326	46	0.01	3	360	60	10	<20	88	<0.01	<10	4	<10	4	37
35	X12490	7.7	0.24	35	40	<5	2.18	19	7	141	1413	3.48	<10	0.79	1945	16	0.01	3	800	222	10	<20	80	<0.01	<10	4	<10	7	1378
QC DATA:																													
Repeat:																													
1	X12456	2.4	0.83	15	55	<5	0.94	2	8	154	2201	3.81	<10	0.63	619	15	0.02	3	990	20	<5	<20	68	<0.01	<10	14	<10	5	57
10	X12465	4.9	0.45	20	50	<5	1.65	3	12	122	3930	4.89	<10	0.40	528	38	0.02	<1	800	20	5	<20	249	<0.01	<10	12	<10	3	37
19	X12474	2.1	0.78	10	75	<5	2.58	2	8	97	1702	3.50	<10	0.51	998	10	0.01	2	1030	14	<5	<20	244	<0.01	<10	16	<10	5	50
Resplit:																													
1	X12456	2.4	0.91	15	55	<5	1.06	3	9	153	2175	3.79	<10	0.71	618	15	0.02	2	1030	26	<5	<20	68	<0.01	<10	16	<10	6	67
Standard:																													
PB113A		11.8	0.23	50	55	<5	1.66	32	2	<1	2239	1.02	<10	0.10	1516	69	0.01	<1	100	5608	10	<20	84	<0.01	<10	6	<10	1	7091

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/n5718S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5721

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

3-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07222
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10742	0.30	0.009
2	X10743	0.40	0.012
3	X10744	0.94	0.027
4	X10745	0.35	0.010
5	X10746	0.62	0.018
6	X10747	0.41	0.012
7	X10748	0.42	0.012
8	X10749	0.32	0.009
9	X10750	0.61	0.018
10	X10751	0.30	0.009
11	X10752	0.36	0.010
12	X10753	0.58	0.017
13	X10754	0.49	0.014
14	X10755	0.21	0.006
15	X10756	0.27	0.008
16	X10757	0.27	0.008
17	X10758	0.30	0.009
18	X10759	0.17	0.005
19	X10760	0.23	0.007
20	X10761	0.33	0.010
21	X10762	0.24	0.007
22	X10763	0.42	0.012
23	X10764	0.33	0.010
24	X10765	0.51	0.015
25	X10766	0.86	0.025
26	X10767	0.40	0.012
27	X10768	0.54	0.016
28	X10769	0.49	0.014
29	X10770	0.54	0.016

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5721 3-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X10771	<0.03	<0.001
31	X10772	0.59	0.017
32	X10773	0.27	0.008
33	X10774	0.28	0.008
34	X10775	0.25	0.007
35	X10776	0.36	0.010

QC DATA:

Repeat:

1	X10742	0.29	0.008
3	X10744	0.94	0.027
10	X10751	0.25	0.007
19	X10760	0.23	0.007

Resplits:

1	X10742	0.24	0.007

Standard:

OXK48		3.51	0.102

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5721

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07222
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10742	4.1	0.71	<5	50	<5	3.55	2	10	58	1049	3.45	<10	0.59	2446	17	0.01	5	470	28	15	<20	232	0.03	<10	12	<10	2	89
2	X10743	3.7	0.79	<5	60	<5	2.55	2	8	64	1500	3.15	<10	0.66	1413	14	0.01	4	940	30	15	<20	177	0.03	<10	15	<10	5	86
3	X10744	11.4	0.50	10	45	<5	2.44	2	13	87	4923	3.97	<10	0.39	1235	21	0.01	6	610	36	20	<20	190	0.02	<10	13	<10	4	52
4	X10745	6.2	0.44	20	45	<5	1.86	1	9	83	2092	3.29	<10	0.29	1030	12	0.01	4	890	32	5	<20	143	0.02	<10	9	<10	4	41
5	X10746	3.3	0.92	<5	55	<5	2.18	2	9	74	2207	3.66	<10	0.88	1112	12	0.01	5	850	28	20	<20	181	0.02	<10	19	<10	4	84
6	X10747	3.5	0.82	10	55	<5	2.95	2	10	65	1920	2.76	<10	0.67	1442	22	0.01	3	1030	28	20	<20	220	0.02	<10	13	<10	6	66
7	X10748	4.1	0.87	15	65	<5	3.12	2	10	90	2209	3.24	<10	0.70	1620	24	0.01	5	840	32	15	<20	214	0.03	<10	14	<10	6	73
8	X10749	4.6	0.57	25	50	<5	2.33	2	12	79	2077	4.02	<10	0.42	1404	15	0.01	6	840	28	20	<20	149	0.03	<10	10	<10	4	61
9	X10750	5.3	0.65	15	50	<5	3.12	2	11	83	2385	3.27	<10	0.49	1619	14	0.01	4	840	24	15	<20	199	0.03	<10	11	<10	5	54
10	X10751	3.4	0.74	<5	60	<5	3.74	2	9	73	907	2.74	<10	0.65	2065	14	<0.01	3	930	22	10	<20	248	0.03	<10	12	<10	5	55
11	X10752	6.8	0.55	15	40	<5	2.40	3	10	111	1784	4.02	<10	0.67	2120	13	0.01	6	790	28	15	<20	152	0.03	<10	12	<10	3	56
12	X10753	6.1	0.63	15	55	<5	2.27	2	11	86	2344	3.51	<10	0.60	1504	12	0.01	6	830	22	15	<20	167	0.02	<10	12	<10	5	52
13	X10754	4.8	0.58	15	50	<5	1.25	3	11	58	1833	4.00	<10	0.65	1106	24	0.01	5	1040	26	20	<20	77	0.02	<10	11	<10	5	43
14	X10755	2.6	0.72	5	55	<5	1.19	<1	10	66	895	2.61	<10	0.80	1075	21	<0.01	3	1050	22	10	<20	72	0.03	<10	11	<10	4	57
15	X10756	4.8	0.37	35	55	<5	2.38	2	10	61	1791	3.67	<10	0.82	2384	16	0.01	4	890	18	15	<20	121	0.03	<10	8	<10	5	24
16	X10757	3.7	0.56	15	50	<5	1.54	2	10	61	1248	2.87	<10	0.63	1560	25	0.01	2	1060	20	10	<20	86	0.03	<10	9	<10	6	47
17	X10758	5.6	0.24	30	40	<5	1.32	3	13	95	1788	4.27	<10	0.07	827	16	0.01	4	800	30	15	<20	88	0.02	<10	6	<10	2	25
18	X10759	3.9	0.27	55	45	<5	0.73	2	12	67	1523	4.44	<10	<0.01	329	15	<0.01	4	1040	26	15	<20	65	0.02	<10	8	<10	5	15
19	X10760	9.9	0.24	150	45	<5	1.91	5	12	93	2283	4.72	<10	0.05	1290	21	<0.01	5	740	32	80	<20	134	0.03	<10	6	<10	3	48
20	X10761	7.9	0.22	30	45	<5	1.71	2	12	104	2836	4.22	<10	0.05	963	13	0.01	4	590	30	20	<20	123	0.03	<10	6	<10	3	15
21	X10762	7.5	0.25	40	50	<5	1.62	3	11	96	1948	4.19	<10	0.01	761	10	0.01	5	800	26	20	<20	120	0.02	<10	8	<10	4	15
22	X10763	4.1	0.58	25	50	<5	1.79	2	12	64	1526	4.33	<10	0.40	1072	13	0.01	5	970	20	20	<20	154	0.03	<10	12	<10	3	32
23	X10764	4.6	0.51	<5	50	<5	1.38	1	9	151	2336	2.56	<10	0.40	725	25	0.01	5	350	18	15	<20	126	0.01	<10	8	<10	3	32
24	X10765	3.9	1.11	<5	55	<5	2.36	2	11	75	2487	3.89	<10	0.90	1230	13	<0.01	5	840	28	25	<20	200	0.02	<10	18	<10	4	71
25	X10766	6.1	0.72	10	70	<5	1.75	1	12	88	3632	3.46	<10	0.45	776	12	<0.01	4	540	28	10	<20	159	0.02	<10	10	<10	4	42

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10767	4.2	0.59	10	50	<5	1.10	2	11	70	1981	3.48	<10	0.36	536	17	0.01	4	1030	24	10	<20	84	0.02	<10	10	<10	5	32
27	X10768	4.2	0.74	10	60	<5	2.06	2	13	79	2142	4.53	<10	0.50	1009	14	0.01	6	910	26	15	<20	152	0.03	<10	13	<10	5	42
28	X10769	3.4	0.68	5	45	<5	1.91	2	11	101	2203	3.68	<10	0.46	896	14	0.01	5	810	24	15	<20	137	0.02	<10	14	<10	4	38
29	X10770	4.6	0.68	10	55	<5	2.82	3	11	77	2544	3.63	<10	0.45	1567	37	0.01	8	1100	24	35	<20	179	0.01	<10	13	<10	5	45
30	X10771	<0.2	0.02	20	<5	<5	>10	<1	2	4	6	0.03	<10	2.01	27	<1	<0.01	<1	30	10	10	<20	8585	0.02	<10	3	<10	<1	<1
31	X10772	4.8	1.06	10	80	<5	3.72	2	10	87	2137	3.52	<10	1.04	2409	20	0.01	4	800	30	15	<20	242	0.03	<10	20	<10	7	84
32	X10773	2.9	0.68	20	55	<5	2.49	2	10	76	1464	3.78	<10	0.58	1520	15	0.02	3	980	26	10	<20	133	0.04	<10	14	<10	5	56
33	X10774	3.2	1.16	20	65	<5	0.96	3	22	60	2713	3.47	20	0.65	194	201	0.03	9	400	80	20	<20	71	0.04	<10	46	<10	8	271
34	X10775	2.5	0.81	20	60	<5	2.53	3	10	59	1420	3.29	<10	0.75	1478	21	0.01	6	1000	26	35	<20	132	0.02	<10	17	<10	4	66
35	X10776	3.4	0.72	5	60	<5	2.58	<1	10	75	2040	2.69	<10	0.59	1214	15	0.02	2	1000	24	<5	<20	6585	0.03	<10	11	<10	5	56
QC DATA:																													
Repeat:																													
1	X10742	4.1	0.72	<5	65	<5	3.56	2	10	59	1051	3.45	<10	0.59	2452	16	0.01	5	490	32	20	<20	249	0.03	<10	12	<10	3	90
10	X10751	3.4	0.76	5	60	<5	3.78	1	9	74	931	2.77	<10	0.67	2095	15	0.01	3	930	24	15	<20	262	0.03	<10	12	<10	5	56
19	X10760	9.8	0.25	160	45	<5	1.84	6	12	95	2330	4.83	<10	0.06	1322	22	<0.01	6	770	32	80	<20	137	0.02	<10	7	<10	4	49
Resplit:																													
1	X10742	4.3	0.85	<5	70	<5	3.55	3	10	55	1129	3.56	<10	0.64	2409	17	0.01	6	460	26	25	<20	232	0.03	<10	14	<10	3	100
Standard:																													
PB113A		11.1	0.26	50	55	<5	1.62	41	2	6	2317	1.03	<10	0.10	1494	70	0.02	3	50	5594	20	<20	86	0.01	<10	7	<10	<1	6937

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5725S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5722

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

3-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07226
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X12421	1.58	0.046
2	X12422	1.17	0.034
3	X12423	0.57	0.017
4	X12424	0.74	0.022
5	X12425	0.96	0.028
6	X12426	0.89	0.026
7	X12427	0.67	0.020
8	X12428	0.84	0.024
9	X12429	0.87	0.025
10	X12430	0.84	0.024
11	X12431	1.02	0.030
12	X12432	0.93	0.027
13	X12433	0.70	0.020
14	X12434	0.75	0.022
15	X12435	0.87	0.025
16	X12436	0.80	0.023
17	X12437	0.90	0.026
18	X12438	1.65	0.048
19	X12439	0.66	0.019
20	X12440	1.03	0.030
21	X12441	0.97	0.028
22	X12442	0.71	0.021
23	X12443	0.50	0.015
24	X12444	<0.03	<0.001
25	X12445	0.07	0.002
26	X12446	0.58	0.017
27	X12447	0.60	0.017
28	X12448	0.40	0.012
29	X12449	0.42	0.012

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5722 3-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X12450	<0.03	<0.001
31	X12451	0.38	0.011
32	X12452	0.39	0.011
33	X12453	0.50	0.015
34	X12454	0.43	0.013
35	X12455	0.32	0.009

QC DATA:

Repeat:

1	X12421	1.51	0.044
10	X12430	0.84	0.024
18	X12438	1.74	0.051
19	X12439	0.67	0.020

Resplits:

1	X12421	1.64	0.048

Standard:

OXK48		3.53	0.103

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 2007-5722

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07226
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X12421	12.8	0.84	15	50	<5	1.06	1	12	155	2613	5.34	<10	0.46	1044	14	<0.01	6	620	72	<5	<20	57	0.03	<10	13	<10	<1	75
2	X12422	3.7	0.60	10	50	<5	0.87	2	18	110	4023	6.01	<10	0.27	586	25	<0.01	6	470	38	5	<20	73	0.03	<10	10	<10	<1	49
3	X12423	1.8	0.73	25	55	<5	1.45	<1	10	138	2295	4.17	<10	0.52	577	26	<0.01	4	670	34	<5	<20	119	0.03	<10	13	<10	2	52
4	X12424	2.5	0.80	10	35	<5	0.65	<1	10	101	2962	4.76	<10	0.50	446	13	<0.01	4	630	38	5	<20	52	0.03	<10	12	<10	<1	51
5	X12425	2.6	0.48	15	50	<5	1.05	2	14	128	3312	4.98	<10	0.31	647	22	<0.01	6	610	62	<5	<20	101	0.03	<10	10	<10	1	50
6	X12426	3.3	0.46	20	25	<5	1.84	<1	12	90	3284	4.39	<10	0.35	485	13	0.01	2	550	40	<5	<20	871	0.03	<10	9	<10	1	36
7	X12427	2.2	0.28	20	40	<5	0.79	1	12	127	2593	5.32	<10	0.10	541	42	<0.01	5	500	34	<5	<20	83	0.03	<10	8	<10	<1	55
8	X12428	5.8	0.25	45	40	<5	0.19	<1	12	110	3817	5.61	<10	<0.01	84	48	<0.01	3	450	42	<5	<20	31	0.03	<10	6	<10	<1	33
9	X12429	3.5	0.29	10	45	<5	0.27	2	14	109	2953	7.29	<10	<0.01	152	23	<0.01	4	510	64	<5	<20	28	0.04	<10	6	<10	<1	72
10	X12430	2.9	0.73	25	55	<5	1.06	3	11	78	2507	4.66	<10	0.49	917	16	<0.01	4	770	78	10	<20	78	0.03	<10	12	<10	2	211
11	X12431	4.9	0.36	15	55	<5	0.70	3	15	145	4801	4.20	<10	0.06	453	59	<0.01	6	360	38	10	<20	80	0.02	<10	7	<10	1	121
12	X12432	3.4	0.44	10	45	<5	1.01	<1	15	124	3997	4.55	<10	0.23	512	20	<0.01	5	440	40	<5	<20	107	0.03	<10	8	<10	<1	37
13	X12433	2.8	0.51	15	50	<5	1.11	<1	14	118	3227	4.21	<10	0.32	555	44	<0.01	3	500	40	<5	<20	113	0.03	<10	10	<10	2	22
14	X12434	2.2	0.75	15	50	<5	1.16	1	12	197	2176	4.53	<10	0.52	650	63	<0.01	8	640	38	10	<20	98	0.03	<10	12	<10	3	31
15	X12435	1.9	0.96	20	60	<5	0.73	<1	10	118	2110	3.50	<10	0.66	557	20	<0.01	5	690	40	10	<20	61	0.02	<10	12	<10	3	43
16	X12436	5.8	0.62	30	35	<5	0.60	<1	12	169	2457	4.64	<10	0.37	516	19	<0.01	7	520	36	<5	<20	39	0.03	<10	10	<10	<1	35
17	X12437	3.2	0.81	25	55	<5	0.99	<1	10	132	3231	3.52	<10	0.71	752	16	<0.01	3	710	34	10	<20	82	0.03	<10	13	<10	3	70
18	X12438	5.0	0.61	15	50	<5	0.48	<1	13	223	5183	4.02	<10	0.38	331	22	<0.01	7	500	44	<5	<20	49	0.02	<10	11	<10	2	38
19	X12439	1.8	1.15	15	65	<5	1.21	<1	10	120	1466	3.81	<10	0.86	720	14	0.01	2	940	46	5	<20	104	0.03	<10	21	<10	3	60
20	X12440	3.6	1.26	95	85	<5	0.72	3	17	67	3266	3.93	20	0.49	269	237	0.03	13	400	166	40	<20	44	0.04	<10	47	<10	5	162
21	X12441	2.6	0.87	10	45	<5	1.62	1	24	169	2273	5.01	<10	0.47	597	23	0.01	6	760	56	10	<20	139	0.03	<10	20	<10	2	53
22	X12442	1.8	1.04	20	60	<5	1.37	<1	10	117	1680	3.63	<10	0.71	692	20	0.01	4	870	42	15	<20	124	0.02	<10	23	<10	3	51
23	X12443	2.1	1.13	15	70	<5	1.25	<1	13	173	2053	4.28	<10	0.80	684	11	<0.01	3	830	50	<5	<20	82	0.04	<10	20	<10	3	53
24	X12444	0.2	3.77	20	780	35	3.88	2	34	65	23	6.76	<10	3.87	1350	6	0.02	5	790	96	25	<20	309	0.16	<10	186	<10	4	97
25	X12445	0.3	2.93	25	235	45	4.46	2	34	54	15	6.58	<10	2.54	1377	7	0.02	5	1030	78	40	<20	145	0.15	<10	148	<10	8	109

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X12446	1.9	1.14	80	65	<5	1.60	1	12	105	1786	4.26	<10	0.73	846	19	<0.01	5	860	50	10	<20	64	0.04	<10	15	<10	4	65
27	X12447	2.5	1.29	15	55	<5	1.39	<1	9	150	2586	4.15	<10	0.95	811	16	<0.01	6	780	158	20	<20	69	0.03	<10	20	<10	3	60
28	X12448	2.0	0.96	10	55	<5	1.40	<1	11	118	2192	4.85	<10	0.64	608	15	<0.01	5	610	46	5	<20	114	0.03	<10	18	<10	<1	49
29	X12449	1.5	0.97	20	50	<5	2.27	2	10	134	1674	3.98	<10	0.58	528	22	0.01	8	830	42	35	<20	190	0.01	<10	18	<10	3	50
30	X12450	<0.2	0.02	45	<5	<5	>10	<1	2	3	5	0.04	<10	1.74	43	<1	<0.01	<1	40	6	5	<20	6372	0.01	<10	2	<10	<1	<1
31	X12451	1.8	0.78	15	50	<5	1.50	2	13	122	1894	4.49	<10	0.64	782	16	<0.01	4	760	48	5	<20	110	0.03	<10	15	<10	2	77
32	X12452	2.3	0.89	20	55	<5	1.83	<1	11	189	2187	3.94	<10	0.69	998	16	<0.01	6	770	78	10	<20	149	0.03	<10	15	<10	4	69
33	X12453	2.2	0.69	30	60	<5	1.61	3	11	115	2356	4.22	<10	0.57	790	28	<0.01	5	780	60	15	<20	135	0.02	<10	17	<10	4	46
34	X12454	2.5	0.68	30	50	<5	1.08	1	14	155	2291	3.97	<10	0.55	720	16	<0.01	6	610	50	5	<20	87	0.02	<10	13	<10	3	40
35	X12455	1.5	0.92	10	190	<5	1.64	<1	8	103	1198	3.66	<10	0.85	995	14	0.01	2	820	42	10	<20	143	0.03	<10	21	<10	4	65
QC DATA:																													
Repeat:																													
1	X12421	12.3	0.78	15	45	<5	1.06	2	12	145	2619	5.32	<10	0.45	1039	13	<0.01	5	600	68	<5	<20	60	0.03	<10	12	<10	<1	73
10	X12430	3.0	0.67	15	45	<5	1.07	3	11	73	2506	4.66	<10	0.49	922	16	<0.01	4	800	78	10	<20	78	0.03	<10	10	<10	2	212
19	X12439	1.7	1.09	15	60	<5	1.21	<1	9	111	1464	3.76	<10	0.85	717	14	<0.01	3	940	42	10	<20	99	0.03	<10	20	<10	2	60
Resplit:																													
1	X12421	12.5	0.75	15	60	<5	1.07	3	12	144	2760	5.34	<10	0.45	1036	13	<0.01	7	600	76	5	<20	60	0.03	<10	12	<10	<1	81
Standard:																													
Pb113A		11.0	0.28	50	65	<5	1.66	37	3	7	2209	1.06	<10	0.09	1475	70	0.02	2	100	5618	25	<20	89	0.02	<10	8	<10	<1	7078

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5722S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5723

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07220
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10672	0.30	0.009
2	X10673	0.33	0.010
3	X10674	0.48	0.014
4	X10675	0.39	0.011
5	X10676	0.29	0.008
6	X10677	0.20	0.006
7	X10678	0.56	0.016
8	X10679	1.12	0.033
9	X10680	1.18	0.034
10	X10681	0.26	0.008
11	X10682	0.21	0.006
12	X10683	0.19	0.006
13	X10684	0.16	0.005
14	X10685	0.75	0.022
15	X10686	1.31	0.038
16	X10687	0.22	0.006
17	X10688	0.15	0.004
18	X10689	0.12	0.003
19	X10690	0.15	0.004
20	X10691	0.28	0.008
21	X10692	0.31	0.009
22	X10693	0.39	0.011
23	X10694	0.66	0.019
24	X10695	1.28	0.037
25	X10696	1.54	0.045
26	X10697	1.31	0.038
27	X10698	0.35	0.010
28	X10699	0.34	0.010
29	X10700	0.91	0.027

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5723 4-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X10701	0.29	0.008
31	X10702	0.69	0.020
32	X10703	1.25	0.036
33	X10704	0.77	0.022
34	X10705	<0.03	<0.001
35	X10706	0.57	0.017

QC DATA:

Repeat:

1	X10672	0.30	0.009
8	X10679	1.01	0.029
9	X10680	1.20	0.035
10	X10681	0.19	0.006
15	X10686	1.34	0.039
19	X10690	0.14	0.004
24	X10695	1.25	0.036
25	X10696	1.58	0.046
32	X10703	1.29	0.038
33	X10704	0.79	0.023

Resplits:

1	X10672	0.34	0.010

Standard:

OXK48		3.49	0.102

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5723

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07220
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10672	3.4	0.25	<5	40	<5	0.64	<1	14	115	2673	5.73	<10	0.05	330	22	0.01	4	690	60	<5	<20	78	0.03	<10	11	<10	<1	21
2	X10673	4.8	0.22	5	40	<5	0.87	3	17	148	4505	5.48	<10	0.08	463	57	0.01	7	250	76	<5	<20	82	0.03	<10	7	<10	<1	78
3	X10674	3.0	0.78	10	50	<5	1.73	2	14	128	2347	4.24	<10	0.55	944	28	<0.01	4	760	82	<5	<20	117	0.03	<10	15	<10	3	117
4	X10675	3.8	0.28	30	35	<5	0.28	1	16	114	2624	5.44	<10	<0.01	75	15	<0.01	5	850	46	<5	<20	22	0.03	<10	9	<10	<1	35
5	X10676	4.6	0.18	85	40	<5	0.14	<1	12	159	2599	6.58	<10	<0.01	52	14	<0.01	4	310	28	5	<20	21	0.03	<10	7	<10	<1	18
6	X10677	4.5	0.20	110	50	<5	0.13	1	18	149	2795	7.87	<10	<0.01	31	55	<0.01	7	330	30	15	<20	26	0.04	<10	6	<10	<1	18
7	X10678	5.2	0.24	10	50	<5	0.38	2	13	186	6822	5.83	<10	<0.01	183	45	<0.01	6	370	78	<5	<20	48	0.03	<10	8	<10	<1	94
8	X10679	1.7	1.05	25	40	<5	0.73	1	12	119	1685	5.40	<10	0.71	664	20	<0.01	7	680	36	15	<20	54	0.02	<10	16	<10	<1	63
9	X10680	2.3	0.70	20	40	<5	0.64	<1	13	157	2018	5.15	<10	0.35	413	23	<0.01	5	690	34	<5	<20	54	0.03	<10	12	<10	<1	45
10	X10681	3.2	0.22	10	30	<5	0.15	<1	11	168	3128	5.26	<10	<0.01	42	14	<0.01	6	430	26	<5	<20	28	0.03	<10	7	<10	<1	6
11	X10682	5.3	0.20	50	45	<5	0.12	<1	13	173	3689	5.98	<10	<0.01	24	19	<0.01	5	340	28	5	<20	35	0.03	<10	6	<10	<1	16
12	X10683	3.5	0.31	25	60	<5	0.18	1	14	169	1855	6.58	<10	<0.01	48	19	<0.01	6	450	26	<5	<20	43	0.03	<10	8	<10	<1	8
13	X10684	2.6	0.21	60	50	<5	0.13	1	12	139	222	7.29	<10	<0.01	25	18	<0.01	6	440	32	15	<20	35	0.03	<10	6	<10	<1	12
14	X10685	3.3	0.19	100	45	<5	0.10	<1	12	161	283	6.03	<10	<0.01	25	20	<0.01	5	310	42	<5	<20	75	0.03	<10	6	<10	<1	16
15	X10686	5.8	0.17	175	45	<5	0.28	3	10	136	464	9.07	<10	<0.01	72	39	<0.01	7	110	122	25	<20	122	0.04	<10	6	<10	<1	39
16	X10687	3.2	0.18	55	55	10	0.17	<1	13	162	273	5.47	<10	<0.01	49	19	<0.01	5	340	36	<5	<20	85	0.03	<10	5	<10	<1	12
17	X10688	4.6	0.17	95	40	<5	0.18	<1	11	165	978	5.67	<10	<0.01	50	41	<0.01	5	440	52	10	<20	63	0.02	<10	6	<10	<1	15
18	X10689	4.9	0.27	115	45	<5	0.14	1	18	182	372	5.89	<10	<0.01	30	35	0.01	6	510	38	20	<20	54	0.03	<10	6	<10	<1	13
19	X10690	3.8	0.24	45	50	15	0.20	<1	20	148	259	9.00	<10	<0.01	23	41	<0.01	4	770	62	<5	<20	31	0.04	<10	5	<10	<1	15
20	X10691	5.3	0.18	60	55	40	0.26	4	23	124	294	>10	<10	<0.01	37	38	<0.01	10	1030	160	20	<20	29	0.05	<10	6	<10	<1	42
21	X10692	5.0	0.22	25	40	<5	0.16	<1	13	119	1758	6.15	<10	<0.01	31	33	<0.01	5	530	34	<5	<20	29	0.03	<10	7	<10	<1	8
22	X10693	4.5	0.22	20	35	<5	0.17	<1	15	163	2778	5.28	<10	<0.01	52	22	<0.01	6	500	30	<5	<20	25	0.03	<10	8	<10	<1	12
23	X10694	5.3	0.26	5	30	<5	0.13	2	17	177	4454	5.35	<10	<0.01	40	52	<0.01	7	360	62	<5	<20	30	0.03	<10	10	<10	<1	50
24	X10695	7.7	0.29	20	40	<5	0.19	2	13	158	6764	4.86	<10	0.04	129	35	<0.01	6	270	78	<5	<20	39	0.02	<10	8	<10	<1	57
25	X10696	4.7	0.54	20	40	<5	0.20	<1	14	147	3164	4.70	<10	0.23	216	27	<0.01	4	420	40	<5	<20	23	0.03	<10	10	<10	<1	53

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10697	6.2	0.29	<5	45	<5	0.20	2	18	164	4827	6.57	<10	0.01	117	15	<0.01	7	420	52	<5	<20	31	0.03	<10	9	<10	<1	41
27	X10698	5.0	0.30	15	30	<5	0.21	<1	10	147	3010	5.34	<10	0.05	152	14	<0.01	4	310	46	<5	<20	36	0.03	<10	8	<10	<1	38
28	X10699	4.8	0.19	10	35	<5	0.18	<1	13	152	3559	5.91	<10	<0.01	57	22	<0.01	4	410	60	<5	<20	23	0.03	<10	6	<10	<1	37
29	X10700	5.5	0.20	10	35	<5	0.16	6	14	135	3829	6.69	<10	<0.01	48	62	<0.01	9	440	114	15	<20	17	0.02	<10	7	<10	<1	171
30	X10701	3.3	0.94	45	55	<5	0.86	1	19	48	2574	3.07	<10	0.48	170	181	0.02	7	410	70	5	<20	56	0.04	<10	38	<10	4	286
31	X10702	5.6	0.17	10	30	<5	0.08	1	10	150	4568	4.49	<10	<0.01	44	22	<0.01	4	200	40	<5	<20	9	0.02	<10	5	<10	<1	38
32	X10703	3.2	0.48	10	40	<5	0.27	2	11	143	2276	4.72	<10	0.25	320	32	<0.01	5	350	28	5	<20	29	0.02	<10	10	<10	<1	52
33	X10704	3.2	0.40	5	30	<5	0.22	3	10	125	2175	4.75	<10	0.22	218	33	0.01	11	400	24	30	<20	19	<0.01	<10	11	<10	<1	39
34	X10705	<0.2	0.02	45	<5	<5	>10	<1	2	4	6	0.03	<10	1.74	27	<1	<0.01	<1	40	6	10	<20	6525	0.02	<10	4	<10	<1	<1
35	X10706	4.2	0.30	15	35	<5	0.23	<1	11	148	3815	4.75	<10	0.12	127	13	<0.01	5	400	22	<5	<20	36	0.02	<10	8	<10	<1	30
QC DATA:																													
Repeat:																													
1	X10672	3.3	0.28	<5	35	<5	0.65	1	13	118	2725	5.77	<10	0.06	332	20	0.01	4	680	58	<5	<20	74	0.03	<10	11	<10	<1	21
10	X10681	3.0	0.24	10	35	<5	0.15	<1	11	172	3057	5.26	<10	<0.01	42	14	<0.01	6	440	28	<5	<20	29	0.02	<10	9	<10	<1	7
19	X10690	3.6	0.24	40	45	10	0.19	1	19	145	251	8.92	<10	<0.01	22	41	<0.01	6	750	56	5	<20	29	0.04	<10	6	<10	<1	14
Resplit:																													
1	X10672	3.4	0.26	<5	35	<5	0.70	1	12	112	2784	5.26	<10	0.05	350	18	0.01	7	600	56	<5	<20	73	0.02	<10	10	<10	<1	22
Standard:																													
Pb113A		11.9	0.26	45	60	<5	1.69	39	3	7	2259	1.05	<10	0.09	1418	67	0.01	2	110	5878	20	<20	81	0.02	<10	8	<10	<1	7095

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5722S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com


CERTIFICATE OF ASSAY AS 2007- 5724

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07227
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X06008	0.56	0.016
2	X06009	0.68	0.020
3	X06010	0.28	0.008
4	X06011	0.40	0.012
5	X06012	0.23	0.007
6	X06013	<0.03	<0.001
7	X06014	0.34	0.010
8	X06015	0.41	0.012
9	X06016	0.21	0.006
10	X06017	0.30	0.009
11	X06018	0.39	0.011
12	X06019	0.26	0.008
13	X06020	0.39	0.011
14	X06021	0.19	0.006
15	X06022	0.31	0.009
16	X06023	0.35	0.010
17	X06024	0.37	0.011
18	X06025	0.52	0.015
19	X06026	0.28	0.008
20	X06027	0.46	0.013
21	X06028	0.28	0.008
22	X06029	0.44	0.013
23	X06030	0.25	0.007
24	X06031	0.37	0.011
25	X06032	0.72	0.021
26	X10812	0.47	0.014
27	X10813	0.50	0.015
28	X10814	0.73	0.021



ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS2007-5724 4-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	X10815	0.32	0.009
30	X10816	0.39	0.011
31	X10817	0.41	0.012
32	X10818	0.25	0.007
33	X10819	0.49	0.014
34	X10820	1.27	0.037
35	X10821	0.32	0.009

QC DATA:

Repeat:

1	X06008	0.56	0.016
10	X06017	0.30	0.009
19	X06026	0.28	0.008

Resplits:

1	X06008	0.52	0.015

Standard:

OXK48		2.52	0.073

AU: 30g FA/AA-Finish

JJ/kk
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5724

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07227
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X06008	3.5	1.28	<5	75	<5	2.21	1	15	77	3256	4.15	<10	1.20	874	24	0.02	8	1050	38	20	<20	136	0.03	<10	77	<10	5	79
2	X06009	3.2	1.29	<5	105	<5	5.41	1	14	73	3498	3.82	<10	1.18	1645	29	0.02	6	1050	34	15	<20	271	0.04	<10	63	<10	9	90
3	X06010	2.0	1.18	<5	120	<5	3.24	<1	16	45	1701	3.38	<10	0.93	1155	73	0.02	5	1510	30	10	<20	179	0.04	<10	54	<10	6	81
4	X06011	2.4	1.18	<5	80	<5	2.72	2	21	50	2184	4.68	<10	1.02	977	49	0.03	6	1270	34	15	<20	182	0.05	<10	93	<10	3	91
5	X06012	1.5	1.14	10	90	<5	3.85	2	14	57	1460	3.64	<10	1.04	1239	52	0.03	6	1280	36	20	<20	592	0.04	<10	68	<10	4	85
6	X06013	<0.2	0.03	30	<5	<5	>10	<1	2	6	4	0.04	<10	1.92	36	<1	<0.01	<1	50	8	30	<20	6170	<0.01	<10	3	<10	<1	22
7	X06014	2.2	1.02	<5	125	<5	3.69	2	12	74	1829	4.05	<10	0.77	1280	44	0.02	6	1090	36	15	<20	303	0.04	<10	51	<10	3	82
8	X06015	2.2	0.78	5	150	<5	2.14	2	11	97	2009	3.38	<10	0.54	757	29	0.02	4	800	30	10	<20	173	0.03	<10	44	<10	4	81
9	X06016	1.3	1.04	5	140	<5	2.30	<1	12	56	1188	3.51	<10	0.80	813	29	0.02	4	1320	30	10	<20	193	0.04	<10	41	<10	4	70
10	X06017	1.8	1.01	<5	120	<5	3.08	1	11	54	1391	3.70	<10	0.71	1037	66	0.02	5	1290	32	10	<20	219	0.04	<10	32	<10	4	66
11	X06018	2.3	1.07	15	125	<5	3.37	3	11	68	1822	3.30	<10	0.81	1301	42	0.02	7	1210	34	30	<20	204	0.03	<10	44	<10	4	89
12	X06019	1.7	0.91	<5	145	<5	2.88	1	10	67	1502	3.23	<10	0.60	1006	28	0.02	3	1020	30	10	<20	187	0.05	<10	36	<10	4	69
13	X06020	2.1	0.83	10	105	<5	2.88	2	10	79	1745	2.70	<10	0.56	995	18	0.02	4	760	30	10	<20	168	0.04	<10	26	<10	4	75
14	X06021	1.1	0.73	10	100	<5	3.04	1	8	82	850	2.45	<10	0.43	1022	19	0.02	4	930	24	15	<20	123	0.04	<10	21	<10	4	56
15	X06022	1.4	0.75	5	315	<5	2.41	1	9	89	1382	3.00	<10	0.53	761	24	0.03	4	840	28	5	<20	201	0.05	<10	42	<10	4	66
16	X06023	1.7	0.93	15	145	<5	2.20	2	12	121	1866	3.49	<10	0.80	726	39	0.04	5	750	32	15	<20	277	0.06	<10	64	<10	4	98
17	X06024	1.8	0.84	5	230	<5	2.11	1	9	67	1891	3.06	<10	0.67	747	34	0.03	4	870	32	10	<20	186	0.06	<10	47	<10	3	83
18	X06025	2.4	0.88	10	125	<5	1.86	1	11	70	2732	3.25	<10	0.67	734	21	0.03	4	760	36	10	<20	110	0.05	<10	56	<10	3	68
19	X06026	1.6	0.80	<5	210	<5	2.11	<1	8	80	1283	2.82	<10	0.56	712	38	0.03	4	910	28	10	<20	132	0.05	<10	35	<10	3	66
20	X06027	7.2	0.73	5	105	<5	2.98	12	11	70	1975	2.48	<10	0.43	1202	40	0.02	3	880	522	10	<20	125	0.04	<10	21	<10	5	959
21	X06028	3.2	1.17	35	65	<5	0.99	3	22	59	2700	3.55	20	0.66	198	210	0.04	10	430	70	15	<20	69	0.05	<10	47	<10	6	278
22	X06029	2.3	0.91	<5	230	<5	2.03	3	10	76	1729	3.30	<10	0.70	751	44	0.03	6	890	30	25	<20	162	0.05	<10	39	<10	2	78
23	X06030	1.9	0.88	10	115	<5	1.64	2	10	91	1314	3.10	<10	0.68	714	27	0.03	4	860	30	15	<20	106	0.05	<10	33	<10	4	79
24	X06031	1.8	0.86	10	155	<5	2.34	1	8	77	1717	2.51	<10	0.62	866	22	0.02	4	790	26	15	<20	156	0.05	<10	28	<10	5	73
25	X06032	3.9	0.74	10	75	<5	2.68	<1	12	84	3635	2.36	<10	0.47	834	37	0.01	3	670	28	<5	<20	127	0.04	<10	17	<10	4	48

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10812	3.0	1.20	<5	50	<5	1.84	1	11	86	1669	3.49	<10	1.65	1404	27	0.02	6	1270	32	20	<20	160	0.03	<10	35	<10	5	82
27	X10813	4.5	1.17	<5	45	<5	1.08	1	14	98	1555	4.93	<10	1.39	973	30	0.01	8	1270	36	20	<20	108	0.03	<10	37	<10	4	94
28	X10814	29.7	0.35	35	45	<5	0.95	2	11	119	4625	4.34	<10	0.32	677	13	0.01	7	880	72	20	<20	104	0.02	<10	14	<10	3	30
29	X10815	25.6	0.28	45	50	<5	0.76	3	11	176	6012	3.53	<10	0.17	550	9	0.01	6	230	38	35	<20	84	0.02	<10	8	<10	2	28
30	X10816	13.6	0.20	20	45	<5	0.57	1	8	142	2489	2.69	<10	0.08	434	9	<0.01	6	550	40	10	<20	83	0.01	<10	8	<10	3	16
31	X10817	11.0	0.22	25	40	<5	0.29	1	10	186	2964	3.54	<10	0.01	158	11	0.01	7	460	32	10	<20	121	0.01	<10	8	<10	2	11
32	X10818	2.9	0.94	10	40	<5	2.59	2	11	143	1381	3.26	<10	0.76	1434	13	0.02	5	830	30	20	<20	279	0.03	<10	17	<10	6	74
33	X10819	2.0	0.93	<5	55	<5	2.27	3	13	132	2268	4.04	<10	0.74	865	13	0.02	8	680	28	30	<20	285	0.01	<10	29	<10	3	70
34	X10820	4.1	0.92	<5	55	<5	1.83	2	16	121	5108	4.41	<10	0.68	678	10	0.02	5	530	26	10	<20	279	0.02	<10	32	<10	2	71
35	X10821	2.0	0.88	<5	65	<5	2.15	1	15	90	1997	3.65	<10	0.68	797	10	0.02	4	850	30	5	<20	323	0.02	<10	24	<10	4	74
QC DATA:																													
Repeat:																													
1	X06008	3.6	1.34	<5	75	<5	2.29	<1	16	82	3387	4.31	<10	1.25	908	24	0.02	8	1110	42	20	<20	150	0.04	<10	80	<10	6	81
10	X06017	1.8	1.02	10	130	<5	3.05	1	12	56	1360	3.68	<10	0.71	1023	61	0.02	5	1290	34	15	<20	221	0.04	<10	33	<10	6	65
19	X06026	1.7	0.83	<5	225	<5	2.14	1	7	82	1302	2.86	<10	0.59	721	34	0.03	4	910	28	15	<20	138	0.05	<10	36	<10	4	66
Resplit:																													
1	X06008	3.4	1.35	<5	75	<5	2.06	1	15	72	3278	4.33	<10	1.32	863	24	0.02	7	1130	40	25	<20	132	0.04	<10	86	<10	6	84
Standard:																													
PB113A		11.6	0.28	45	70	<5	1.62	32	3	7	2305	1.09	<10	0.11	1466	66	0.02	3	70	5520	20	<20	80	0.02	<10	8	<10	<1	7011

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5674S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5725

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Dec-07

No. of samples received: 19
Sample Type: Core
Project: KSM
Shipment #: 07238
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X14421	0.34	0.010
2	X14422	0.28	0.008
3	X14423	0.29	0.008
4	X14424	0.25	0.007
5	X14425	0.24	0.007
6	X14426	0.19	0.006
7	X14427	0.28	0.008
8	X14428	0.16	0.005
9	X14429	<0.03	<0.001
10	X14430	0.30	0.009
11	X14431	0.21	0.006
12	X14432	0.36	0.010
13	X14433	0.38	0.011
14	X14434	0.37	0.011
15	X14435	0.25	0.007
16	X14436	0.19	0.006
17	X14437	0.40	0.012
18	X14438	0.31	0.009
19	X14439	0.50	0.015
QC DATA:			
Repeat:			
1	X14421	0.33	0.010
11	X14431	0.22	0.006
13	X14433	0.38	0.011
14	X14434	0.37	0.011
17	X14437	0.43	0.013
18	X14438	0.36	0.010

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5725 4-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
Standard:			
OXK48		3.52	0.103

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5725

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 19
Sample Type: Core
Project: KSM
Shipment #: 07238
Submitted by: Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X14421	1.4	1.36	<5	105	<5	2.02	2	13	77	1075	3.25	10	1.28	781	55	0.04	5	1250	38	15	<20	130	0.08	<10	64	<10	4	74
2	X14422	1.4	1.25	<5	90	<5	2.42	2	15	71	973	4.03	10	1.12	869	45	0.03	5	1280	40	15	<20	117	0.09	<10	71	<10	6	75
3	X14423	1.7	1.30	<5	105	<5	2.05	1	13	89	1301	3.17	<10	1.20	789	56	0.03	4	1160	38	15	<20	132	0.08	<10	59	<10	6	67
4	X14424	1.2	1.31	<5	90	<5	3.59	2	13	72	1115	4.07	10	1.25	914	59	0.03	4	1150	36	15	<20	256	0.09	<10	96	<10	8	67
5	X14425	1.2	1.28	<5	130	<5	2.01	2	15	69	1183	3.99	10	1.18	738	61	0.04	6	1340	40	25	<20	136	0.09	<10	83	<10	7	74
6	X14426	1.4	1.24	<5	80	<5	2.61	2	14	80	935	3.47	10	1.10	805	293	0.04	4	1270	40	10	<20	162	0.08	<10	62	<10	5	81
7	X14427	0.9	1.24	<5	125	<5	1.67	2	14	60	964	3.96	10	1.04	631	62	0.05	6	1400	36	10	<20	121	0.08	<10	85	<10	6	77
8	X14428	1.2	1.23	<5	105	<5	1.48	4	15	74	879	3.78	<10	1.07	671	93	0.05	9	1310	34	45	<20	146	0.05	<10	81	<10	6	93
9	X14429	<0.2	0.02	10	<5	<5	>10	<1	2	2	2	0.03	<10	1.89	22	<1	<0.01	<1	60	8	<5	<20	6439	0.03	<10	2	<10	<1	<1
10	X14430	3.2	1.16	30	55	<5	0.93	3	21	60	2650	3.53	20	0.63	182	189	0.03	8	370	78	10	<20	74	0.06	<10	45	<10	7	271
11	X14431	1.1	1.16	<5	85	<5	3.42	3	15	63	871	5.26	10	1.04	824	70	0.04	8	1230	34	30	<20	308	0.08	<10	92	<10	4	99
12	X14432	1.7	1.38	<5	75	<5	1.58	3	15	79	1307	4.54	10	1.31	781	45	0.03	6	1240	62	20	<20	152	0.09	<10	93	<10	7	121
13	X14433	2.8	1.39	<5	90	<5	1.91	2	14	81	1747	4.22	<10	1.28	842	87	0.03	5	1200	44	15	<20	197	0.08	<10	97	<10	6	146
14	X14434	2.6	1.25	<5	75	<5	2.80	2	15	68	1191	3.99	10	1.09	960	90	0.03	6	1320	56	20	<20	135	0.08	<10	71	<10	5	120
15	X14435	1.7	1.30	<5	65	<5	2.38	2	16	76	1302	3.68	10	1.16	833	70	0.04	6	1320	48	10	<20	187	0.09	<10	65	<10	7	131
16	X14436	1.5	1.34	<5	75	<5	2.14	3	16	79	1028	3.66	10	1.27	782	71	0.05	7	1370	46	40	<20	171	0.08	<10	77	<10	7	115
17	X14437	1.6	1.17	<5	85	<5	2.10	2	14	82	1374	4.06	10	1.06	591	60	0.04	6	1180	36	20	<20	240	0.08	<10	75	<10	6	72
18	X14438	1.7	1.01	<5	75	<5	2.63	1	13	82	1401	3.64	<10	0.81	591	108	0.03	3	1210	36	<5	<20	246	0.07	<10	53	<10	6	73
19	X14439	2.3	0.67	5	60	<5	3.34	<1	12	107	1777	2.54	<10	0.38	528	260	0.02	2	1230	26	<5	<20	216	0.07	<10	30	<10	7	30
QC DATA:																													
Repeat:																													
1	X14421	1.4	1.37	<5	105	<5	2.03	2	13	77	1098	3.26	<10	1.30	789	51	0.04	5	1270	42	20	<20	148	0.08	<10	64	<10	6	74
11	X14431	1.3	1.14	<5	80	<5	3.39	3	15	60	853	5.21	10	1.02	819	64	0.04	9	1220	38	35	<20	316	0.08	<10	90	<10	5	99
Resplit:																													
1	X14421	1.3	1.42	<5	105	<5	2.15	2	14	82	1000	3.50	<10	1.32	830	55	0.05	10	1330	40	20	<20	141	0.07	<10	71	<10	6	74

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
Standard:																													
PB113A		11.2	0.26	55	65	<5	1.60	30	3	6	2302	1.01	<10	0.10	1470	63	0.02	3	70	5510	20	<20	85	0.01	<10	7	<10	<1	6937

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5725S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5726

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Dec-07

No. of samples received: 20
Sample Type: Core
Project: KSM
Shipment #: 07239
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10822	0.48	0.014
2	X10823	1.16	0.034
3	X10824	0.46	0.013
4	X10825	0.82	0.024
5	X10826	0.47	0.014
6	X10827	0.58	0.017
7	X10828	0.65	0.019
8	X10829	0.27	0.008
9	X10830	<0.03	<0.001
10	X10831	0.41	0.012
11	X10832	0.34	0.010
12	X10833	0.48	0.014
13	X10834	0.61	0.018
14	X10835	0.58	0.017
15	X10836	1.85	0.054
16	X10837	0.61	0.018
17	X10838	0.59	0.017
18	X10839	0.41	0.012
19	X10840	0.43	0.013
20	X12590	0.44	0.013

QC DATA:

Repeat:

1	X10822	0.52	0.015
2	X10823	1.14	0.033
4	X10825	0.77	0.022
5	X10826	0.46	0.013
6	X10827	0.48	0.014

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5726 4-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
7	X10828	0.64	0.019
8	X10829	0.30	0.009
17	X10838	0.68	0.020
19	X10840	0.38	0.011
Resplits:			
1	X10822	0.55	0.016
Standard:			
OXK48		3.51	0.102

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5726

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 20
Sample Type: Core
Project: KSM
Shipment #: 07239
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10822	2.3	1.18	15	50	<5	1.17	<1	16	160	1756	4.57	<10	0.97	821	25	0.02	5	870	44	10	<20	154	0.03	<10	28	<10	3	90
2	X10823	3.7	0.96	15	50	<5	1.00	<1	14	121	4011	4.34	<10	0.79	778	12	0.01	4	730	32	<5	<20	127	0.03	<10	24	<10	2	80
3	X10824	1.8	1.11	20	55	<5	1.15	<1	11	159	1339	4.11	<10	0.97	956	15	0.01	4	850	38	<5	<20	128	0.03	<10	28	<10	3	99
4	X10825	1.7	1.17	20	65	<5	0.97	1	15	94	1246	4.27	<10	1.02	689	15	0.01	5	900	38	20	<20	127	0.03	<10	27	<10	2	103
5	X10826	3.0	0.74	20	50	<5	1.40	<1	16	150	1764	4.80	<10	0.83	1158	10	0.01	6	820	36	5	<20	122	0.03	<10	26	<10	3	51
6	X10827	3.0	0.83	20	50	<5	1.67	<1	10	128	1430	3.68	<10	0.92	1360	13	0.01	3	860	32	<5	<20	133	0.03	<10	21	<10	3	55
7	X10828	6.7	0.48	10	45	<5	1.38	1	13	163	2902	6.40	<10	0.40	1063	13	0.01	7	710	54	5	<20	118	0.04	<10	16	<10	2	15
8	X10829	4.3	0.59	20	50	<5	1.22	3	12	131	1682	4.49	<10	0.57	1056	25	0.02	11	810	50	35	<20	100	0.01	<10	20	<10	2	39
9	X10830	<0.2	0.03	45	<5	<5	>10	<1	2	6	4	0.04	<10	1.92	27	<1	<0.01	<1	60	10	10	<20	6820	0.01	<10	3	<10	<1	<1
10	X10831	5.9	0.57	<5	40	<5	1.25	2	14	131	1192	8.21	<10	0.51	1352	15	0.02	8	950	106	10	<20	88	0.05	<10	16	<10	<1	39
11	X10832	8.9	0.32	50	30	<5	1.24	2	10	204	3613	4.76	<10	0.45	1067	18	0.01	6	440	106	20	<20	96	0.03	<10	11	<10	<1	33
12	X10833	7.5	0.31	60	45	<5	2.47	3	10	247	6501	4.95	<10	0.96	2037	10	0.01	9	200	50	30	<20	191	0.03	<10	12	<10	2	71
13	X10834	4.9	0.48	30	35	<5	2.16	3	12	126	3117	4.53	<10	0.73	1487	11	0.01	4	680	42	10	<20	154	0.04	<10	15	<10	4	105
14	X10835	3.3	0.69	25	15	<5	1.26	<1	12	203	2616	4.25	<10	0.63	827	10	0.01	7	640	26	5	<20	107	0.03	<10	28	<10	<1	57
15	X10836	4.0	1.28	80	75	<5	1.04	2	23	70	8657	4.31	<10	0.62	211	730	0.04	69	290	94	45	<20	87	0.03	<10	49	<10	6	82
16	X10837	1.9	1.23	30	65	<5	1.50	<1	13	141	1114	4.54	<10	0.98	958	15	0.02	4	740	42	15	<20	223	0.03	<10	34	<10	4	80
17	X10838	2.6	0.99	25	55	<5	0.97	<1	13	180	2156	4.54	<10	0.79	705	12	0.02	6	800	40	20	<20	111	0.03	<10	28	<10	3	71
18	X10839	1.8	1.20	35	75	<5	1.32	2	10	120	1343	3.66	<10	1.00	899	18	0.02	10	780	40	40	<20	217	0.01	<10	35	<10	3	79
19	X10840	1.7	1.07	<5	35	<5	0.76	1	11	151	1346	3.94	<10	0.91	627	14	0.02	7	730	30	15	<20	80	0.02	<10	30	<10	2	49
20	X12590	1.3	0.95	<5	85	<5	2.61	2	11	86	1288	2.69	<10	0.59	840	82	0.02	4	940	38	<5	<20	147	0.08	<10	25	<10	9	65
QC DATA:																													
Repeat:																													
1	X10822	2.1	1.23	20	55	<5	1.20	<1	16	170	1733	4.54	<10	0.96	814	24	0.02	4	850	44	10	<20	158	0.03	<10	30	<10	3	89
10	X10831	6.0	0.64	<5	50	<5	1.18	3	15	125	1207	8.15	<10	0.57	1280	19	0.02	8	980	100	15	<20	91	0.02	<10	18	<10	<1	35
Resplit:																													
1	X10822	1.9	1.22	20	45	<5	1.25	1	11	148	1657	4.68	<10	1.02	797	22	0.02	8	920	40	15	<20	146	0.01	<10	28	<10	3	80

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
Standard:																													
PB113A		11.4	0.26	45	75	<5	1.69	36	3	6	2214	1.01	<10	0.11	1352	69	0.02	2	90	5500	15	<20	85	0.02	<10	8	<10	<1	6976

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5722S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5726R

Revised

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Dec-07

No. of samples received: 20
Sample Type: Core
Project: KSM
Shipment #: 07239
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10822	0.48	0.014
2	X10823	1.16	0.034
3	X10824	0.46	0.013
4	X10825	0.82	0.024
5	X10826	0.47	0.014
6	X10827	0.58	0.017
7	X10828	0.65	0.019
8	X10829	0.27	0.008
9	X10830	<0.03	<0.001
10	X10831	0.41	0.012
11	X10832	0.34	0.010
12	X10833	0.48	0.014
13	X10834	0.61	0.018
14	X10835	0.58	0.017
15	X10836	1.85	0.054
16	X10837	0.61	0.018
17	X10838	0.59	0.017
18	X10839	0.41	0.012
19	X10840	0.43	0.013
20	X12596	0.44	0.013

QC DATA:

Repeat:

1	X10822	0.52	0.015
2	X10823	1.14	0.033
4	X10825	0.77	0.022
5	X10826	0.46	0.013
6	X10827	0.48	0.014

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5726R 4-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
7	X10828	0.64	0.019
8	X10829	0.30	0.009
17	X10838	0.68	0.020
19	X10840	0.38	0.011
Resplits:			
1	X10822	0.55	0.016
Standard:			
OXK48		3.51	0.102

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5726R
Revised

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 20
Sample Type: Core
Project: KSM
Shipment #: 07239
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10822	2.3	1.18	15	50	<5	1.17	<1	16	160	1756	4.57	<10	0.97	821	25	0.02	5	870	44	10	<20	154	0.03	<10	28	<10	3	90
2	X10823	3.7	0.96	15	50	<5	1.00	<1	14	121	4011	4.34	<10	0.79	778	12	0.01	4	730	32	<5	<20	127	0.03	<10	24	<10	2	80
3	X10824	1.8	1.11	20	55	<5	1.15	<1	11	159	1339	4.11	<10	0.97	956	15	0.01	4	850	38	<5	<20	128	0.03	<10	28	<10	3	99
4	X10825	1.7	1.17	20	65	<5	0.97	1	15	94	1246	4.27	<10	1.02	689	15	0.01	5	900	38	20	<20	127	0.03	<10	27	<10	2	103
5	X10826	3.0	0.74	20	50	<5	1.40	<1	16	150	1764	4.80	<10	0.83	1158	10	0.01	6	820	36	5	<20	122	0.03	<10	26	<10	3	51
6	X10827	3.0	0.83	20	50	<5	1.67	<1	10	128	1430	3.68	<10	0.92	1360	13	0.01	3	860	32	<5	<20	133	0.03	<10	21	<10	3	55
7	X10828	6.7	0.48	10	45	<5	1.38	1	13	163	2902	6.40	<10	0.40	1063	13	0.01	7	710	54	5	<20	118	0.04	<10	16	<10	2	15
8	X10829	4.3	0.59	20	50	<5	1.22	3	12	131	1682	4.49	<10	0.57	1056	25	0.02	11	810	50	35	<20	100	0.01	<10	20	<10	2	39
9	X10830	<0.2	0.03	45	<5	<5	>10	<1	2	6	4	0.04	<10	1.92	27	<1	<0.01	<1	60	10	10	<20	6820	0.01	<10	3	<10	<1	<1
10	X10831	5.9	0.57	<5	40	<5	1.25	2	14	131	1192	8.21	<10	0.51	1352	15	0.02	8	950	106	10	<20	88	0.05	<10	16	<10	<1	39
11	X10832	8.9	0.32	50	30	<5	1.24	2	10	204	3613	4.76	<10	0.45	1067	18	0.01	6	440	106	20	<20	96	0.03	<10	11	<10	<1	33
12	X10833	7.5	0.31	60	45	<5	2.47	3	10	247	6501	4.95	<10	0.96	2037	10	0.01	9	200	50	30	<20	191	0.03	<10	12	<10	2	71
13	X10834	4.9	0.48	30	35	<5	2.16	3	12	126	3117	4.53	<10	0.73	1487	11	0.01	4	680	42	10	<20	154	0.04	<10	15	<10	4	105
14	X10835	3.3	0.69	25	15	<5	1.26	<1	12	203	2616	4.25	<10	0.63	827	10	0.01	7	640	26	5	<20	107	0.03	<10	28	<10	<1	57
15	X10836	4.0	1.28	80	75	<5	1.04	2	23	70	8657	4.31	<10	0.62	211	730	0.04	69	290	94	45	<20	87	0.03	<10	49	<10	6	82
16	X10837	1.9	1.23	30	65	<5	1.50	<1	13	141	1114	4.54	<10	0.98	958	15	0.02	4	740	42	15	<20	223	0.03	<10	34	<10	4	80
17	X10838	2.6	0.99	25	55	<5	0.97	<1	13	180	2156	4.54	<10	0.79	705	12	0.02	6	800	40	20	<20	111	0.03	<10	28	<10	3	71
18	X10839	1.8	1.20	35	75	<5	1.32	2	10	120	1343	3.66	<10	1.00	899	18	0.02	10	780	40	40	<20	217	0.01	<10	35	<10	3	79
19	X10840	1.7	1.07	<5	35	<5	0.76	1	11	151	1346	3.94	<10	0.91	627	14	0.02	7	730	30	15	<20	80	0.02	<10	30	<10	2	49
20	X12596	1.3	0.95	<5	85	<5	2.61	2	11	86	1288	2.69	<10	0.59	840	82	0.02	4	940	38	<5	<20	147	0.08	<10	25	<10	9	65
QC DATA:																													
Repeat:																													
1	X10822	2.1	1.23	20	55	<5	1.20	<1	16	170	1733	4.54	<10	0.96	814	24	0.02	4	850	44	10	<20	158	0.03	<10	30	<10	3	89
10	X10831	6.0	0.64	<5	50	<5	1.18	3	15	125	1207	8.15	<10	0.57	1280	19	0.02	8	980	100	15	<20	91	0.02	<10	18	<10	<1	35
Resplit:																													
1	X10822	1.9	1.22	20	45	<5	1.25	1	11	148	1657	4.68	<10	1.02	797	22	0.02	8	920	40	15	<20	146	0.01	<10	28	<10	3	80

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
Standard:																													
PB113A		11.4	0.26	45	75	<5	1.69	36	3	6	2214	1.01	<10	0.11	1352	69	0.02	2	90	5500	15	<20	85	0.02	<10	8	<10	<1	6976

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5722S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5727

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07234
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X14281	0.29	0.008
2	X14282	0.50	0.015
3	X14283	0.11	0.003
4	X14284	0.11	0.003
5	X14285	0.22	0.006
6	X14286	0.19	0.006
7	X14287	0.23	0.007
8	X14288	0.18	0.005
9	X14289	0.23	0.007
10	X14290	0.16	0.005
11	X14291	0.18	0.005
12	X14292	1.63	0.048
13	X14293	0.18	0.005
14	X14294	1.45	0.042
15	X14295	<0.03	<0.001
16	X14296	1.22	0.036
17	X14297	0.17	0.005
18	X14298	0.22	0.006
19	X14299	0.31	0.009
20	X14300	0.18	0.005
21	X14301	0.14	0.004
22	X14302	0.17	0.005
23	X14303	0.42	0.012
24	X14304	0.36	0.010
25	X14305	0.20	0.006
26	X14306	0.26	0.008
27	X14307	0.28	0.008
28	X14308	0.42	0.012
29	X14309	0.27	0.008

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5727 4-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X14310	0.56	0.016
31	X14311	0.28	0.008
32	X14312	1.04	0.030
33	X14313	0.78	0.023
34	X14314	0.60	0.017
35	X14315	0.48	0.014

QC DATA:

Repeat:

1	X14281	0.22	0.006
10	X14290	0.20	0.006
14	X14294	1.49	0.043
16	X14296	1.18	0.034
19	X14299	0.37	0.011
33	X14313	0.69	0.020

Resplits:

1	X14281	0.24	0.007

Standard:

OXK48		3.56	0.104

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5727

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1


No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07234
Submitted by: Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X14281	3.9	1.03	<5	35	<5	0.43	4	17	68	1537	4.42	<10	0.66	473	55	0.01	9	1030	84	10	<20	15	<0.01	<10	22	<10	1	218
2	X14282	6.3	0.93	<5	45	<5	0.71	8	24	107	2092	4.86	<10	0.78	762	55	0.01	8	940	144	15	<20	41	0.01	<10	17	<10	3	442
3	X14283	2.0	0.69	<5	15	<5	0.65	2	17	89	1244	3.69	<10	0.52	587	120	<0.01	6	920	108	15	<20	34	<0.01	<10	11	<10	<1	58
4	X14284	3.6	0.72	60	45	<5	0.74	4	15	118	1078	3.49	<10	0.39	535	72	<0.01	5	1040	88	85	<20	69	0.01	<10	12	<10	2	104
5	X14285	7.7	0.75	70	30	<5	2.12	22	17	101	1811	4.36	<10	0.54	1107	114	<0.01	7	1220	198	130	<20	518	0.01	<10	19	<10	4	1316
6	X14286	3.2	0.72	<5	40	<5	3.99	10	17	130	1276	3.84	<10	0.54	761	86	<0.01	7	1170	178	15	<20	491	0.01	<10	19	<10	4	493
7	X14287	1.9	0.81	<5	30	<5	3.89	2	15	107	1078	3.52	<10	0.74	648	117	<0.01	9	1280	78	25	<20	470	<0.01	<10	23	<10	3	69
8	X14288	2.7	0.77	<5	35	<5	4.13	8	16	115	886	3.54	<10	0.60	659	205	0.01	7	1200	726	5	<20	523	0.02	<10	20	<10	4	596
9	X14289	4.2	0.75	15	10	<5	4.35	12	16	103	1385	4.30	<10	0.59	889	86	0.02	5	1100	280	20	<20	494	0.03	<10	22	<10	2	814
10	X14290	2.3	0.44	10	30	<5	4.21	6	15	182	935	3.46	<10	0.19	351	86	0.02	7	1110	324	15	<20	506	0.02	<10	14	<10	3	314
11	X14291	6.6	0.50	<5	20	<5	4.22	34	15	112	995	3.61	<10	0.34	529	90	0.01	5	1150	2024	10	<20	547	0.05	<10	19	<10	3	2541
12	X14292	0.2	0.65	2210	100	90	0.90	3	32	29	60	4.93	20	2.05	793	8	0.19	110	1020	38	25	<20	83	0.10	<10	27	<10	12	50
13	X14293	5.0	0.60	15	35	<5	4.65	2	14	174	948	3.87	<10	0.39	626	65	0.01	8	1180	324	15	<20	534	0.06	<10	20	<10	5	116
14	X14294	4.8	0.83	45	50	<5	4.95	4	20	140	2759	4.27	<10	0.78	900	107	0.02	6	930	108	15	<20	469	0.09	<10	36	<10	16	216
15	X14295	<0.2	0.03	45	<5	<5	>10	<1	<1	4	5	0.03	<10	2.10	25	<1	<0.01	<1	70	8	30	<20	6279	<0.01	<10	5	<10	<1	<1
16	X14296	2.4	1.07	35	35	<5	4.43	1	14	91	1175	3.27	<10	0.91	684	110	0.02	6	1460	80	15	<20	402	0.09	<10	39	<10	10	93
17	X14297	1.9	1.41	30	10	<5	4.80	7	17	81	829	3.97	10	1.17	927	55	0.02	6	1580	270	15	<20	278	0.10	<10	52	<10	6	377
18	X14298	1.2	1.57	30	45	<5	4.21	2	19	86	580	4.09	10	1.30	807	63	0.04	7	1630	68	35	<20	311	0.09	<10	69	<10	9	58
19	X14299	1.1	1.55	35	25	<5	4.19	1	14	83	717	3.44	<10	1.23	875	69	0.03	6	1520	54	15	<20	334	0.09	<10	55	<10	5	58
20	X14300	1.1	1.50	30	25	<5	4.84	<1	14	73	507	3.21	<10	1.17	1044	37	0.02	6	1560	50	15	<20	297	0.08	<10	42	<10	5	68
21	X14301	1.4	1.40	25	15	<5	3.97	4	14	95	582	3.14	<10	1.14	965	46	0.03	7	1540	184	15	<20	280	0.10	<10	51	<10	5	313
22	X14302	1.3	1.37	25	30	<5	3.46	6	16	83	646	3.53	10	1.14	916	57	0.02	7	1610	176	25	<20	295	0.09	<10	55	<10	7	329
23	X14303	1.6	1.16	30	30	<5	5.07	1	16	88	1226	3.54	<10	0.85	800	166	0.02	6	1380	50	10	<20	361	0.09	<10	43	<10	7	54
24	X14304	2.1	1.18	25	30	<5	4.07	19	15	56	922	3.38	<10	0.90	818	78	0.02	5	1530	270	20	<20	316	0.09	<10	46	<10	9	1191
25	X14305	2.1	1.21	30	30	<5	3.98	29	14	100	800	3.58	10	0.90	854	261	0.02	6	1500	90	15	<20	333	0.09	<10	48	<10	9	1759

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X14306	6.2	0.45	70	10	5	2.73	2	17	82	664	5.53	<10	0.13	169	80	<0.01	4	1040	114	50	<20	375	0.07	<10	19	<10	2	81
27	X14307	1.8	1.41	15	40	<5	1.83	4	19	90	1057	4.00	10	0.93	902	89	0.02	7	1720	64	10	<20	88	0.10	<10	53	<10	11	216
28	X14308	2.6	1.39	25	55	<5	2.56	4	20	84	1341	4.76	10	1.12	1007	103	0.03	10	1570	66	40	<20	98	0.06	<10	61	<10	7	189
29	X14309	2.8	1.12	30	50	<5	1.15	10	18	112	961	3.91	<10	0.71	603	199	0.02	7	1760	150	10	<20	83	0.08	<10	39	<10	12	447
30	X14310	1.4	1.56	20	85	<5	3.50	2	17	59	1281	4.83	10	1.30	1284	97	0.03	5	1430	48	10	<20	142	0.10	<10	84	<10	12	86
31	X14311	1.5	1.36	30	60	<5	1.79	<1	18	83	859	4.12	10	1.00	690	102	0.03	6	1680	76	20	<20	59	0.10	<10	53	<10	7	103
32	X14312	2.7	1.40	5	60	<5	2.82	2	18	81	2396	5.27	10	1.22	1008	89	0.04	6	1110	50	15	<20	131	0.09	<10	101	<10	9	68
33	X14313	1.8	1.46	15	175	<5	1.11	2	17	76	1762	5.24	10	1.26	607	87	0.04	8	1460	44	15	<20	76	0.10	<10	95	<10	8	74
34	X14314	1.3	1.59	15	145	<5	1.66	1	17	74	1308	4.71	10	1.36	705	71	0.04	7	1540	52	20	<20	80	0.11	<10	88	<10	11	74
35	X14315	1.4	1.64	15	60	<5	2.46	1	21	93	1156	4.90	10	1.42	830	110	0.05	6	1580	56	15	<20	111	0.12	<10	85	<10	11	73
QC DATA:																													
Repeat:																													
1	X14281	3.7	1.05	<5	40	<5	0.45	5	18	74	1559	4.51	<10	0.70	492	58	0.01	10	1070	92	20	<20	18	<0.01	<10	25	<10	2	227
10	X14290	2.3	0.51	15	15	<5	4.27	6	16	197	940	3.51	<10	0.20	358	88	0.02	7	1120	332	10	<20	515	0.03	<10	16	<10	5	321
19	X14299	1.1	1.64	20	25	<5	4.28	1	16	92	731	3.51	10	1.26	889	73	0.03	5	1580	62	15	<20	368	0.11	<10	58	<10	9	59
Resplit:																													
1	X14281	3.9	1.05	5	35	<5	0.48	4	19	88	1646	5.05	<10	0.83	506	48	0.01	11	1120	94	10	<20	20	0.01	<10	24	<10	2	209
Standard:																													
PB113A		11.0	0.24	50	70	<5	1.70	39	4	7	2259	1.08	<10	0.12	1446	67	0.02	2	90	5504	20	<20	87	0.02	<10	10	<10	1	6909

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish



ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5722S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5728

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Submitted by:Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X14246	0.16	0.005
2	X14247	0.22	0.006
3	X14248	0.27	0.008
4	X14249	0.28	0.008
5	X14250	0.21	0.006
6	X14251	0.15	0.004
7	X14252	0.13	0.004
8	X14253	0.13	0.004
9	X14254	0.16	0.005
10	X14255	0.46	0.013
11	X14256	0.30	0.009
12	X14257	0.26	0.008
13	X14258	0.28	0.008
14	X14259	0.68	0.020
15	X14260	0.43	0.013
16	X14261	0.07	0.002
17	X14262	0.42	0.012
18	X14263	0.46	0.013
19	X14264	0.65	0.019
20	X14265	0.61	0.018
21	X14266	0.65	0.019
22	X14267	0.60	0.017
23	X14268	0.28	0.008
24	X14269	0.20	0.006
25	X14270	0.26	0.008
26	X14271	0.29	0.008
27	X14272	0.23	0.007
28	X14273	0.28	0.008
29	X14274	0.52	0.015

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5728 4-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X14275	<0.03	<0.001
31	X14276	0.31	0.009
32	X14277	0.15	0.004
33	X14278	0.21	0.006
34	X14279	0.35	0.010
35	X14280	0.78	0.023

QC DATA:

Repeat:

1	X14246	0.14	0.004
10	X14255	0.40	0.012
19	X14264	0.67	0.020

Resplits:

1	X14246	0.13	0.004

Standard:

OXK48		3.53	0.103

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

3-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5728

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Submitted by:Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X14246	0.5	1.54	25	50	30	2.19	<1	15	72	203	3.87	<10	1.45	877	8	0.02	5	1900	60	15	<20	143	0.02	<10	55	<10	7	55
2	X14247	0.5	1.39	10	40	20	2.31	1	16	79	239	4.28	<10	1.27	988	9	0.01	5	1850	48	10	<20	130	0.02	<10	41	<10	5	42
3	X14248	0.6	1.59	15	35	<5	2.47	3	19	66	479	4.91	<10	1.61	1318	54	0.01	10	1660	48	35	<20	137	0.01	<10	48	<10	3	45
4	X14249	0.7	2.18	15	30	<5	0.90	2	19	93	450	5.61	<10	2.37	784	15	0.01	13	1840	58	25	<20	33	0.02	<10	70	<10	1	63
5	X14250	1.4	0.57	<5	60	30	0.29	2	20	126	470	7.52	<10	0.17	76	38	0.01	8	1190	50	10	<20	36	0.02	<10	11	<10	<1	18
6	X14251	1.1	0.47	<5	40	15	0.27	1	18	107	469	5.57	<10	0.13	47	44	<0.01	7	1280	26	<5	<20	20	0.01	<10	10	<10	<1	9
7	X14252	0.6	0.39	10	55	25	0.26	<1	22	99	178	6.87	<10	<0.01	20	125	0.01	5	1240	38	<5	<20	36	0.02	<10	8	<10	<1	3
8	X14253	0.8	0.42	<5	55	20	0.24	2	19	91	409	6.18	<10	0.14	42	48	<0.01	6	1130	42	<5	<20	26	0.01	<10	7	<10	<1	11
9	X14254	0.7	0.66	<5	35	<5	0.29	1	16	105	440	5.08	<10	0.37	98	23	<0.01	5	1340	34	<5	<20	9	<0.01	<10	10	<10	<1	25
10	X14255	2.1	0.80	10	40	<5	0.31	2	17	107	506	6.21	<10	0.46	142	29	<0.01	6	1370	50	<5	<20	19	0.01	<10	12	<10	<1	37
11	X14256	0.6	1.08	20	40	<5	0.31	1	17	111	499	5.66	<10	0.86	233	55	<0.01	8	1330	48	15	<20	16	0.01	<10	16	<10	<1	57
12	X14257	0.6	1.59	20	40	<5	0.41	<1	15	92	696	4.14	<10	1.45	556	18	0.01	5	1370	46	10	<20	20	0.01	<10	27	<10	3	73
13	X14258	1.2	0.85	15	40	<5	0.37	1	22	115	851	5.82	<10	0.53	226	471	<0.01	5	1360	48	10	<20	16	0.01	<10	16	<10	1	44
14	X14259	1.9	0.98	10	35	<5	0.45	6	27	108	1697	6.89	<10	0.75	301	45	<0.01	14	1290	60	25	<20	15	<0.01	<10	25	<10	<1	166
15	X14260	1.1	1.14	10	45	<5	0.39	1	20	107	891	5.20	<10	0.98	335	163	0.01	9	1500	50	5	<20	30	0.02	<10	33	<10	3	62
16	X14261	0.2	0.84	75	130	15	0.22	6	81	257	454	>10	30	0.22	455	119	0.06	415	150	108	15	<20	10	0.04	<10	31	<10	<1	402
17	X14262	1.2	1.03	25	35	<5	0.50	1	17	115	932	3.95	<10	0.84	400	113	<0.01	10	1290	46	<5	<20	29	0.01	<10	23	<10	3	56
18	X14263	1.8	0.85	10	20	<5	0.44	<1	20	106	1401	4.44	<10	0.62	299	60	<0.01	8	1290	36	<5	<20	14	<0.01	<10	16	<10	<1	43
19	X14264	4.5	1.01	10	30	<5	0.67	1	17	110	2033	4.08	<10	0.71	512	36	0.01	6	1180	80	10	<20	24	<0.01	<10	23	<10	3	66
20	X14265	3.9	1.11	30	30	<5	0.41	2	13	115	2028	3.74	<10	0.85	341	36	0.01	7	1280	54	15	<20	14	<0.01	<10	24	<10	2	152
21	X14266	3.7	1.13	20	35	<5	0.46	3	13	118	1889	3.65	<10	0.87	377	39	0.01	9	1310	58	10	<20	34	<0.01	<10	25	<10	4	122
22	X14267	2.2	1.27	15	45	<5	0.61	1	17	100	2158	5.44	<10	1.04	566	46	0.01	7	1140	98	15	<20	27	0.01	<10	29	<10	<1	54
23	X14268	2.0	0.69	25	20	<5	0.45	5	19	120	1742	5.11	<10	0.37	272	105	0.01	6	1110	150	<5	<20	17	<0.01	<10	15	<10	<1	259
24	X14269	2.4	0.59	20	40	<5	0.48	2	15	131	1032	4.65	<10	0.20	231	32	0.01	7	1510	132	<5	<20	37	0.01	<10	13	<10	2	75
25	X14270	2.3	0.87	15	35	<5	0.35	2	13	117	954	3.61	<10	0.56	252	31	0.01	10	1440	46	15	<20	21	<0.01	<10	19	<10	3	50

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X14271	6.2	0.61	30	45	<5	0.40	3	17	105	1987	4.64	<10	0.30	195	28	<0.01	8	1480	118	25	<20	37	0.01	<10	13	<10	3	110
27	X14272	4.0	0.46	15	30	<5	0.38	2	16	123	1943	4.08	<10	0.12	144	41	<0.01	7	1340	44	15	<20	35	<0.01	<10	9	<10	2	69
28	X14273	6.7	0.41	45	40	<5	0.30	2	17	157	1369	4.53	<10	<0.01	101	42	0.01	7	1010	108	35	<20	39	0.01	<10	8	<10	2	37
29	X14274	4.0	0.44	5	45	<5	0.41	3	22	152	1247	4.00	<10	0.04	137	204	0.01	11	1210	536	5	<20	98	<0.01	<10	14	<10	3	57
30	X14275	<0.2	0.02	50	<5	<5	>10	<1	2	3	4	0.02	<10	1.67	21	1	<0.01	<1	50	8	25	<20	6664	<0.01	<10	4	<10	<1	<1
31	X14276	3.6	0.48	<5	40	<5	0.43	3	26	139	2040	5.88	<10	0.08	150	59	0.01	11	1200	62	<5	<20	27	<0.01	<10	15	<10	1	105
32	X14277	2.0	0.46	<5	55	<5	0.33	3	34	118	529	7.48	<10	0.05	99	68	0.01	11	1230	56	10	<20	38	0.02	<10	11	<10	<1	40
33	X14278	4.6	0.54	25	30	<5	0.42	2	20	141	1095	4.30	<10	0.22	226	60	<0.01	8	1230	92	25	<20	29	<0.01	<10	13	<10	1	45
34	X14279	5.4	0.63	15	50	<5	0.50	2	21	112	2222	4.63	<10	0.34	313	61	<0.01	10	1270	80	20	<20	32	0.01	<10	13	<10	3	35
35	X14280	3.8	0.63	25	20	<5	0.47	5	15	138	1866	3.73	<10	0.38	384	82	<0.01	6	1050	136	<5	<20	14	<0.01	<10	11	<10	<1	315
QC DATA:																													
Repeat:																													
1	X14246	0.4	1.49	30	45	35	2.21	<1	15	68	204	3.90	<10	1.46	882	8	0.01	5	1940	52	15	<20	126	0.02	<10	53	<10	5	54
10	X14255	2.1	0.72	5	50	<5	0.31	2	18	102	520	6.26	<10	0.45	141	29	<0.01	6	1370	50	5	<20	23	0.02	<10	11	<10	2	36
19	X14264	4.6	0.99	20	35	<5	0.67	<1	17	102	1990	4.05	<10	0.69	505	39	0.01	8	1210	78	10	<20	29	<0.01	<10	21	<10	3	66
Resplit:																													
1	X14246	0.3	1.45	20	55	30	2.14	1	18	76	194	4.01	<10	1.39	856	10	0.02	7	1920	54	20	<20	136	0.01	<10	51	<10	7	51
Standard:																													
Pb113A		11.8	0.26	50	70	<5	1.63	39	3	7	2283	1.08	<10	0.12	1457	67	0.02	3	90	5564	20	<20	82	0.02	<10	9	<10	<1	6980

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5722S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5729

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07224
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X12351	0.25	0.007
2	X12352	0.22	0.006
3	X12353	0.25	0.007
4	X12354	0.32	0.009
5	X12355	0.35	0.010
6	X12356	0.14	0.004
7	X12357	0.28	0.008
8	X12358	0.27	0.008
9	X12359	0.38	0.011
10	X12360	0.22	0.006
11	X12361	0.59	0.017
12	X12362	1.45	0.042
13	X12363	0.74	0.022
14	X12364	1.57	0.046
15	X12365	1.74	0.051
16	X12366	1.48	0.043
17	X12367	0.79	0.023
18	X12368	0.74	0.022
19	X12369	0.96	0.028
20	X12370	0.93	0.027
21	X12371	1.23	0.036
22	X12372	1.23	0.036
23	X12373	1.52	0.044
24	X12374	0.83	0.024
25	X12375	1.42	0.041
26	X12376	0.74	0.022
27	X12377	0.76	0.022
28	X12378	0.90	0.026
29	X12379	0.70	0.020

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5729 4-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X12380	0.67	0.020
31	X12381	1.83	0.053
32	X12382	0.96	0.028
33	X12383	<0.03	<0.001
34	X12384	0.49	0.014
35	X12385	0.34	0.010
QC DATA:			
Repeat:			
1	X12351	0.26	0.008
10	X12360	0.18	0.005
12	X12362	1.49	0.043
14	X12364	1.56	0.045
15	X12365	1.84	0.054
16	X12366	1.50	0.044
19	X12369	0.96	0.028
Resplits:			
1	X12351	0.20	0.006
Standard:			
OXK48		3.49	0.102

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

4-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5729

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07224
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X12351	1.6	0.82	<5	25	<5	2.59	2	14	122	1268	5.18	<10	0.61	1056	13	0.02	7	830	16	10	<20	136	0.04	<10	70	<10	2	30
2	X12352	1.5	0.99	<5	30	<5	2.03	1	13	104	914	4.71	<10	0.73	752	10	0.02	6	1030	22	15	<20	135	0.04	<10	37	<10	2	38
3	X12353	5.8	0.90	30	20	<5	3.60	<1	11	108	1011	4.38	<10	0.75	1836	10	0.01	5	950	52	5	<20	211	0.04	<10	36	<10	3	49
4	X12354	5.3	1.16	5	35	<5	1.90	2	12	84	901	4.34	<10	1.01	855	11	0.02	6	1120	38	15	<20	116	0.04	<10	51	<10	4	59
5	X12355	1.5	1.11	15	60	<5	1.63	<1	11	89	1024	3.86	<10	0.98	771	7	0.02	2	1040	22	<5	<20	103	0.04	<10	54	<10	4	50
6	X12356	1.1	1.26	<5	60	<5	1.59	2	16	136	791	6.25	<10	1.16	772	11	0.02	9	1240	24	25	<20	109	0.05	<10	187	<10	5	55
7	X12357	2.0	1.34	<5	50	<5	1.46	1	13	114	1722	5.24	<10	1.29	770	14	0.02	7	1070	24	15	<20	89	0.05	<10	156	<10	2	64
8	X12358	1.8	1.01	10	20	<5	3.05	<1	13	124	1298	4.69	<10	0.98	1229	10	0.02	7	880	20	15	<20	129	0.04	<10	62	<10	3	41
9	X12359	2.1	1.15	<5	40	<5	1.25	1	14	139	1877	4.83	<10	1.08	631	13	0.02	8	1070	24	20	<20	77	0.04	<10	104	<10	3	62
10	X12360	1.1	0.99	<5	75	<5	1.22	<1	10	134	1107	3.66	<10	0.97	555	14	0.04	5	970	18	<5	<20	153	0.05	<10	133	<10	3	56
11	X12361	2.9	1.40	<5	60	<5	1.76	3	15	93	2662	4.82	<10	1.35	863	17	0.02	11	1540	30	45	<20	154	0.04	<10	123	<10	5	87
12	X12362	2.0	1.11	<5	35	<5	1.32	<1	10	117	3161	4.04	<10	0.97	1213	12	<0.01	5	1020	42	10	<20	65	0.03	<10	18	<10	3	112
13	X12363	1.6	1.05	<5	45	<5	1.10	2	12	123	1755	4.93	<10	1.10	1031	17	0.03	9	1010	32	20	<20	70	0.04	<10	50	<10	2	108
14	X12364	2.0	0.87	10	30	<5	0.70	<1	12	162	2971	3.61	<10	0.85	650	15	0.02	6	830	30	10	<20	52	0.04	<10	32	<10	2	65
15	X12365	2.9	0.69	<5	25	<5	0.66	1	14	124	4846	4.29	<10	0.65	540	16	0.02	6	670	30	5	<20	48	0.02	<10	24	<10	<1	48
16	X12366	2.1	1.08	5	30	<5	1.16	1	12	110	2690	4.29	<10	0.97	963	15	<0.01	8	1110	38	20	<20	61	0.03	<10	27	<10	2	86
17	X12367	1.4	0.75	<5	35	<5	1.82	2	11	106	1713	3.89	<10	0.85	1323	13	<0.01	6	1060	34	10	<20	94	0.04	<10	25	<10	3	79
18	X12368	1.9	0.80	10	25	<5	1.56	1	12	114	2325	4.40	<10	0.75	1097	15	<0.01	7	1070	22	15	<20	64	0.03	<10	19	<10	2	44
19	X12369	19.7	0.67	170	30	<5	1.77	<1	10	115	1634	3.87	<10	0.80	1419	18	<0.01	5	890	42	40	<20	80	0.05	<10	16	<10	2	74
20	X12370	2.2	0.69	40	25	<5	1.29	2	11	122	3097	4.19	<10	0.82	1061	15	<0.01	8	950	34	30	<20	58	0.03	<10	14	<10	2	65
21	X12371	1.8	0.50	<5	30	<5	0.86	3	12	135	2877	4.12	<10	0.42	664	14	<0.01	5	720	116	<5	<20	63	0.04	<10	13	<10	1	148
22	X12372	1.9	1.09	10	30	<5	0.70	4	11	122	2841	4.37	<10	0.94	615	20	<0.01	8	980	48	30	<20	47	0.02	<10	27	<10	2	73
23	X12373	1.6	0.87	<5	20	<5	0.62	2	14	126	2240	4.42	<10	0.74	586	16	<0.01	7	870	30	15	<20	36	0.03	<10	26	<10	<1	42
24	X12374	1.4	1.04	10	25	<5	0.91	<1	10	112	1434	4.08	<10	1.09	943	14	<0.01	4	1110	28	10	<20	41	0.04	<10	25	<10	3	77
25	X12375	2.6	0.83	120	25	<5	0.95	4	12	123	1865	5.78	<10	0.77	800	15	<0.01	10	950	82	30	<20	57	0.04	<10	24	<10	<1	164

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X12376	2.0	0.72	10	25	<5	1.09	2	10	123	2108	3.49	<10	0.69	740	15	<0.01	6	980	34	15	<20	78	0.03	<10	13	<10	2	90
27	X12377	2.4	0.68	5	25	<5	0.73	2	10	90	2173	3.48	<10	0.63	538	17	<0.01	5	1020	28	10	<20	37	0.03	<10	11	<10	2	98
28	X12378	2.0	0.46	15	25	<5	1.46	2	10	96	1897	3.31	<10	0.59	1191	13	<0.01	5	1090	24	15	<20	78	0.03	<10	8	<10	4	40
29	X12379	2.6	0.44	15	25	<5	1.77	1	11	108	2353	3.49	<10	0.58	1230	16	<0.01	6	880	48	10	<20	104	0.03	<10	7	<10	3	37
30	X12380	1.7	0.76	45	30	<5	1.96	1	9	75	1470	3.12	<10	0.95	1609	30	<0.01	4	1120	22	10	<20	93	0.07	<10	10	<10	5	62
31	X12381	3.9	1.08	35	35	<5	1.01	3	22	57	8724	4.11	<10	0.62	203	604	0.04	64	340	72	40	<20	63	0.02	<10	44	<10	5	73
32	X12382	2.3	0.68	20	30	<5	0.96	2	10	86	2236	3.33	<10	0.51	601	20	<0.01	8	1070	36	35	<20	51	<0.01	<10	6	<10	3	61
33	X12383	<0.2	0.02	20	<5	<5	>10	<1	1	3	2	0.03	<10	2.46	34	<1	<0.01	<1	70	8	15	<20	6403	0.01	<10	5	<10	<1	<1
34	X12384	1.5	1.02	10	40	<5	1.29	<1	8	76	1682	2.60	<10	0.86	912	19	<0.01	3	1130	24	15	<20	66	0.03	<10	10	<10	4	86
35	X12385	1.5	0.67	5	20	<5	4.29	<1	10	122	1571	3.35	<10	0.57	1929	12	<0.01	4	740	22	5	<20	325	0.04	<10	8	<10	9	64
QC DATA:																													
Repeat:																													
1	X12351	1.6	0.80	<5	25	<5	2.60	1	14	119	1268	5.21	<10	0.60	1060	12	0.02	6	840	16	10	<20	132	0.05	<10	68	<10	2	30
10	X12360	1.3	0.98	<5	80	<5	1.21	<1	11	131	1112	3.66	<10	0.97	557	16	0.04	6	980	20	5	<20	151	0.04	<10	130	<10	3	56
19	X12369	20.2	0.65	175	25	<5	1.78	2	10	112	1646	3.89	<10	0.80	1431	15	<0.01	7	880	44	45	<20	75	0.04	<10	16	<10	2	75
Resplit:																													
1	X12351	1.5	0.77	<5	25	<5	2.47	3	13	133	1136	5.09	<10	0.56	1013	11	0.02	10	920	18	15	<20	124	0.04	<10	66	<10	2	28
Standard:																													
PB113A		11.6	0.24	45	50	<5	1.69	38	2	5	2317	1.03	<10	0.10	1430	62	0.01	3	100	5592	20	<20	82	<0.01	<10	7	<10	<1	6975

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5729S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5730

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07229
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X12491	0.57	0.017
2	X12492	0.72	0.021
3	X12493	0.34	0.010
4	X12494	0.56	0.016
5	X12495	0.83	0.024
6	X12496	1.34	0.039
7	X12497	1.27	0.037
8	X12498	1.02	0.030
9	X12499	1.12	0.033
10	X12500	0.96	0.028
11	X12501	0.82	0.024
12	X12502	1.02	0.030
13	X12503	0.95	0.028
14	X12504	0.62	0.018
15	X12505	0.78	0.023
16	X12506	0.53	0.015
17	X12507	0.52	0.015
18	X12508	0.66	0.019
19	X12509	0.30	0.009
20	X12510	0.54	0.016
21	X12511	0.34	0.010
22	X12512	0.46	0.013
23	X12513	0.30	0.009
24	X12514	0.27	0.008
25	X12515	0.35	0.010
26	X12516	0.52	0.015
27	X12517	0.55	0.016
28	X12518	0.35	0.010
29	X12519	0.38	0.011

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5730 4-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X12520	1.83	0.053
31	X12521	<0.03	<0.001
32	X12522	0.28	0.008
33	X12523	0.33	0.010
34	X12524	0.32	0.009
35	X12525	0.07	0.002

QC DATA:

Repeat:

1	X12491	0.62	0.018
2	X12492	0.69	0.020
5	X12495	0.86	0.025
7	X12497	1.30	0.038
8	X12498	1.03	0.030
9	X12499	1.01	0.029
10	X12500	0.91	0.027
19	X12509	0.26	0.008
34	X12524	0.36	0.010

Resplits:

1	X12491	0.59	0.017

Standard:

OXK48		3.56	0.104

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

4-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5730

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1


No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07229
Submitted by: Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X12491	12.0	0.39	20	25	<5	0.93	24	16	104	3513	5.30	<10	0.15	540	23	<0.01	7	980	118	15	<20	57	0.03	<10	9	<10	2	1612
2	X12492	13.1	0.31	15	25	<5	0.91	27	9	103	2729	4.25	<10	0.14	565	24	<0.01	6	740	588	20	<20	71	0.03	<10	6	<10	1	1917
3	X12493	6.8	0.26	10	30	<5	1.90	13	10	180	2456	3.10	<10	0.18	976	22	<0.01	4	490	214	<5	<20	215	0.04	<10	5	<10	5	857
4	X12494	8.1	0.54	15	25	<5	1.37	6	14	127	3083	4.55	<10	0.38	929	25	<0.01	6	980	140	5	<20	124	0.03	<10	10	<10	2	248
5	X12495	4.6	0.86	<5	30	<5	1.27	3	10	108	2766	4.51	<10	0.93	934	21	0.01	7	850	46	20	<20	92	0.05	<10	17	<10	3	78
6	X12496	8.6	0.60	<5	20	<5	0.72	2	12	169	5842	3.49	<10	0.45	496	15	<0.01	6	310	26	5	<20	69	0.04	<10	11	<10	<1	39
7	X12497	12.4	0.65	<5	15	<5	0.77	3	10	131	8010	3.86	<10	0.46	518	18	0.01	7	670	36	20	<20	71	0.03	<10	12	<10	<1	45
8	X12498	18.7	0.41	15	25	<5	0.46	2	18	173	8051	3.64	<10	0.24	351	15	<0.01	9	320	42	15	<20	42	<0.01	<10	7	<10	<1	29
9	X12499	5.2	0.76	<5	25	<5	0.85	<1	11	130	3780	3.20	<10	0.61	551	15	<0.01	5	720	26	5	<20	88	0.03	<10	14	<10	2	52
10	X12500	4.9	1.03	<5	40	<5	1.47	<1	11	127	3522	3.50	<10	0.75	733	22	0.01	5	890	28	5	<20	205	0.03	<10	17	<10	6	92
11	X12501	4.5	1.30	<5	35	<5	1.46	1	10	92	2555	3.76	<10	1.10	891	17	0.01	4	880	28	15	<20	187	0.04	<10	17	<10	3	122
12	X12502	5.9	1.12	<5	40	<5	0.78	<1	11	157	2712	4.17	<10	0.80	593	30	0.02	5	830	26	5	<20	77	0.04	<10	23	<10	2	75
13	X12503	11.0	1.19	35	25	<5	1.14	3	12	91	2721	5.55	<10	0.97	870	34	<0.01	9	700	42	35	<20	114	0.03	<10	34	<10	<1	119
14	X12504	24.1	0.50	25	25	<5	0.67	5	11	122	1949	4.09	<10	0.25	521	32	0.01	6	890	266	<5	<20	55	0.03	<10	9	<10	2	296
15	X12505	8.7	0.96	40	35	<5	0.88	1	9	95	1388	3.76	<10	0.87	1115	69	0.01	5	1090	36	15	<20	58	0.03	<10	14	<10	3	91
16	X12506	6.1	1.03	15	30	<5	0.76	<1	13	71	1461	3.67	<10	0.82	851	29	0.01	5	1120	30	15	<20	47	0.03	<10	14	<10	3	87
17	X12507	4.8	0.90	<5	20	<5	0.77	2	13	58	1812	3.84	<10	0.72	727	52	0.01	5	1020	34	20	<20	49	0.03	<10	12	<10	2	67
18	X12508	3.6	0.80	10	35	<5	1.48	<1	9	102	2153	2.90	<10	0.62	985	18	0.01	3	910	24	5	<20	155	0.04	<10	13	<10	5	43
19	X12509	1.6	1.08	<5	60	<5	1.04	<1	10	46	1222	2.63	<10	0.83	765	34	0.01	2	1150	26	10	<20	98	0.03	<10	15	<10	4	71
20	X12510	2.4	0.89	5	30	<5	0.89	1	13	67	2504	3.64	<10	0.75	701	176	0.01	5	980	32	20	<20	64	0.03	<10	13	<10	3	47
21	X12511	2.5	0.87	15	50	<5	2.24	1	8	92	1437	2.58	<10	1.17	1620	48	0.01	5	910	24	25	<20	148	0.03	<10	13	<10	5	49
22	X12512	1.7	1.08	<5	100	<5	2.67	<1	10	95	1532	2.43	<10	0.65	933	68	0.02	4	1110	26	10	<20	263	0.03	<10	15	<10	5	45
23	X12513	0.9	0.99	10	110	<5	2.97	<1	8	71	952	2.70	<10	0.65	873	32	0.03	3	1050	22	15	<20	343	0.02	<10	22	<10	4	47
24	X12514	0.9	0.93	<5	75	<5	2.88	1	9	75	804	2.83	<10	0.51	803	27	0.03	4	1110	28	10	<20	321	0.03	<10	22	<10	4	50
25	X12515	1.1	0.96	<5	75	<5	2.12	1	9	67	1139	2.97	<10	0.59	670	20	0.03	5	1120	26	20	<20	232	0.03	<10	25	<10	4	42

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X12516	2.0	0.84	<5	50	<5	2.75	<1	9	100	1833	2.58	<10	0.53	901	30	0.02	4	1010	24	10	<20	343	0.03	<10	16	<10	6	36
27	X12517	2.2	0.77	15	40	<5	1.39	<1	9	94	2149	2.70	<10	0.61	682	21	0.02	4	920	30	10	<20	109	0.02	<10	14	<10	4	39
28	X12518	1.5	0.87	30	40	<5	2.23	4	9	165	1451	3.29	<10	0.57	945	16	0.01	8	830	38	25	<20	160	0.03	<10	15	<10	3	98
29	X12519	4.0	1.00	10	75	<5	3.06	<1	8	79	1302	2.44	<10	0.68	1297	12	0.01	3	1070	24	10	<20	215	0.07	<10	15	<10	4	55
30	X12520	4.0	1.06	40	35	<5	1.02	4	23	66	8719	4.19	<10	0.61	203	612	0.05	73	450	76	65	<20	58	<0.01	<10	46	<10	5	76
31	X12521	<0.2	0.02	25	<5	<5	>10	<1	2	2	4	0.03	<10	2.08	25	<1	<0.01	<1	60	10	10	<20	6578	0.01	<10	5	<10	<1	1
32	X12522	3.4	1.05	5	55	<5	2.81	<1	9	84	453	2.67	<10	0.65	1329	20	<0.01	4	1160	22	15	<20	181	0.03	<10	15	<10	3	63
33	X12523	8.5	0.63	50	25	<5	1.51	<1	9	91	1318	3.37	<10	0.35	769	13	0.01	<1	1090	32	<5	<20	81	0.04	<10	12	<10	3	55
34	X12524	23.2	0.40	45	25	<5	0.69	<1	14	156	1201	7.91	<10	<0.01	250	11	0.01	1	990	124	<5	<20	38	0.07	<10	9	<10	<1	94
35	X12525	0.2	1.00	75	155	5	0.30	6	78	299	455	>10	<10	0.19	509	129	0.06	403	130	138	15	<20	13	0.10	<10	30	<10	<1	408
QC DATA:																													
Repeat:																													
1	X12491	12.3	0.40	20	25	<5	0.94	23	16	106	3581	5.39	<10	0.15	552	26	<0.01	8	1010	120	15	<20	55	0.03	<10	9	<10	<1	1634
10	X12500	4.8	1.05	<5	35	<5	1.48	2	11	128	3531	3.51	<10	0.76	734	23	0.01	6	910	26	5	<20	202	<0.01	<10	17	<10	5	91
19	X12509	1.6	1.09	<5	55	<5	1.04	<1	10	47	1203	2.64	<10	0.82	767	33	0.01	3	1170	26	15	<20	90	0.03	<10	15	<10	3	72
Resplit:																													
1	X12491	11.8	0.40	20	30	<5	0.91	22	16	118	3521	5.15	<10	0.16	544	23	0.01	10	1020	122	20	<20	53	0.03	<10	10	<10	1	1562
Standard:																													
PB113A		11.2	0.21	50	60	<5	1.66	37	2	6	2290	1.06	<10	0.11	1440	61	0.02	3	90	5514	20	<20	85	<0.01	<10	9	<10	<1	6935

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish



ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5729S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5731

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07230
Submitted by:Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	X12526	0.27	0.008		
2	X12527	0.21	0.006		
3	X12528	0.30	0.009	126	3.68
4	X12529	0.98	0.029	100	2.92
5	X12530	0.50	0.015		
6	X12531	0.30	0.009		
7	X12532	0.31	0.009		
8	X12533	0.23	0.007		
9	X12534	0.74	0.022		
10	X12535	0.44	0.013		
11	X12536	0.88	0.026	33.9	0.99
12	X12537	0.47	0.014		
13	X12538	0.73	0.021		
14	X12539	0.58	0.017		
15	X12540	0.61	0.018		
16	X12541	0.35	0.010		
17	X12542	0.33	0.010		
18	X12543	0.22	0.006		
19	X12544	0.40	0.012		
20	X12545	0.24	0.007		
21	X12546	0.34	0.010		
22	X12547	0.32	0.009		
23	X12548	0.26	0.008		
24	X12549	0.47	0.014		
25	X12550	0.28	0.008		
26	X12551	0.39	0.011		
27	X12552	0.39	0.011		
28	X12553	0.39	0.011		
29	X12554	0.29	0.008		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5731 4-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
30	X12555	0.42	0.012		
31	X12556	0.52	0.015		
32	X12557	0.55	0.016		
33	X12558	0.69	0.020		
34	X12559	0.23	0.007		
35	X12560	<0.03	<0.001		
QC DATA:					
Repeat:					
1	X12526	0.28	0.008		
3	X12528			126	3.68
10	X12535	0.43	0.013		
19	X12544	0.42	0.012		
33	X12558	0.75	0.022		
Resplits:					
1	X12526	0.32	0.009		
Standard:					
OXK48		3.58	0.104		
Pb113				22.4	0.65

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

4-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5731

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07230
Submitted by:Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X12526	10.6	0.52	20	30	<5	1.90	1	11	93	1940	3.59	<10	0.20	934	16	0.01	5	980	84	10	<20	102	0.03	<10	11	<10	2	59
2	X12527	9.3	0.48	35	20	<5	1.07	5	11	95	984	3.76	<10	0.11	467	31	0.01	5	1220	162	5	<20	63	0.03	<10	11	<10	3	449
3	X12528	>30	0.38	190	20	<5	1.18	7	8	155	1518	3.70	<10	0.01	426	27	<0.01	6	780	200	160	<20	62	0.03	<10	8	<10	1	609
4	X12529	>30	0.33	160	25	<5	2.72	9	8	137	1703	3.30	<10	0.17	1168	27	<0.01	7	950	266	50	<20	94	0.03	<10	9	<10	3	630
5	X12530	24.4	0.39	55	35	<5	2.58	2	11	152	3385	3.36	<10	0.06	1011	12	<0.01	6	810	56	<5	<20	132	0.03	<10	8	<10	3	97
6	X12531	3.0	1.20	40	35	<5	1.02	4	22	57	2717	3.65	10	0.68	204	232	0.04	13	590	76	35	<20	54	0.04	<10	53	<10	5	279
7	X12532	5.2	0.86	35	60	<5	2.17	<1	8	114	1451	2.25	<10	0.51	930	22	0.01	5	990	26	15	<20	131	0.02	<10	13	<10	6	53
8	X12533	1.2	0.86	20	100	<5	2.49	<1	6	66	612	1.67	<10	0.51	1038	22	<0.01	1	1090	22	<5	<20	148	0.03	<10	10	<10	5	47
9	X12534	2.9	0.97	45	45	<5	2.74	1	10	96	2426	2.98	<10	0.70	1126	20	0.01	4	1030	28	20	<20	143	0.03	<10	13	<10	5	58
10	X12535	8.5	0.72	35	35	<5	1.50	6	11	112	1789	3.60	<10	0.35	726	16	0.01	5	1110	262	15	<20	87	0.04	<10	11	<10	3	261
11	X12536	>30	0.59	50	35	<5	1.21	2	10	160	3287	3.41	<10	0.30	703	14	0.01	6	910	42	5	<20	57	0.02	<10	12	<10	3	136
12	X12537	14.6	1.29	55	35	<5	1.39	1	10	113	1608	4.10	<10	1.19	1364	14	0.01	6	1170	42	30	<20	63	0.05	<10	22	<10	3	113
13	X12538	26.7	0.94	80	30	<5	1.22	1	15	109	3752	4.18	<10	0.73	1111	18	0.02	7	1100	40	25	<20	58	0.03	<10	16	<10	3	114
14	X12539	12.6	1.05	120	30	<5	1.12	<1	11	99	1793	3.91	<10	0.83	1150	20	0.02	6	1180	38	25	<20	55	0.03	<10	16	<10	3	126
15	X12540	4.6	0.97	100	25	<5	1.94	6	11	97	761	3.74	<10	0.77	1446	31	0.01	16	1130	42	75	<20	85	<0.01	<10	18	<10	3	173
16	X12541	7.0	0.78	65	20	<5	2.21	2	12	118	1763	3.93	<10	0.46	1311	21	0.01	4	1200	80	<5	<20	87	0.05	<10	14	<10	4	250
17	X12542	5.6	0.83	30	35	<5	2.92	4	9	107	1528	2.72	<10	0.62	1691	43	0.01	13	1020	38	55	<20	115	<0.01	<10	15	<10	4	118
18	X12543	6.5	1.19	50	20	<5	2.37	<1	11	85	916	4.04	<10	0.92	1585	12	0.01	4	1400	74	10	<20	84	0.04	<10	17	<10	2	124
19	X12544	4.8	1.13	35	30	<5	1.83	2	10	94	1341	3.45	<10	0.90	1188	19	0.01	7	1140	34	25	<20	75	0.03	<10	17	<10	4	95
20	X12545	2.7	0.84	30	40	<5	2.65	<1	9	91	898	2.46	<10	0.46	1206	19	0.01	3	1130	26	5	<20	149	0.04	<10	16	<10	6	60
21	X12546	0.9	1.01	30	40	<5	3.24	<1	10	122	930	3.03	<10	0.56	1003	20	0.03	4	1050	36	10	<20	285	0.06	<10	21	<10	6	66
22	X12547	2.6	0.88	5	40	<5	2.65	2	8	103	3675	2.95	<10	0.48	822	15	0.02	4	1000	42	10	<20	209	0.03	<10	18	<10	7	49
23	X12548	0.9	0.97	10	125	<5	2.36	<1	8	112	979	2.69	<10	0.54	792	18	0.03	5	1070	28	15	<20	194	0.04	<10	22	<10	7	58
24	X12549	1.8	0.78	10	50	<5	2.64	<1	7	119	1722	2.25	<10	0.41	739	10	0.02	4	920	26	<5	<20	192	0.04	<10	15	<10	7	41
25	X12550	2.1	1.17	10	110	<5	2.02	<1	10	108	1710	2.63	<10	0.68	770	12	0.02	5	1140	32	20	<20	145	0.05	<10	19	<10	8	71

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AS 2007-5731 Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X12551	3.5	0.95	20	50	<5	2.78	<1	10	94	1535	2.55	<10	0.61	1179	17	<0.01	3	1010	30	15	<20	134	0.05	<10	15	<10	7	84
27	X12552	8.4	0.51	30	30	<5	1.72	7	11	116	2200	5.13	<10	0.16	559	15	<0.01	7	1020	262	15	<20	63	0.05	<10	9	<10	4	307
28	X12553	5.7	0.81	45	40	<5	2.16	5	10	115	1403	3.12	<10	0.42	724	17	0.01	5	1160	104	20	<20	93	0.06	<10	12	<10	6	205
29	X12554	5.1	0.99	25	35	<5	2.35	<1	12	100	1297	3.33	<10	0.53	850	21	<0.01	4	1180	80	20	<20	93	0.07	<10	14	<10	6	91
30	X12555	18.2	0.70	45	25	<5	1.89	7	12	115	1870	3.58	<10	0.30	715	24	0.01	5	1250	150	10	<20	66	0.07	<10	12	<10	6	364
31	X12556	2.9	1.21	45	60	<5	4.32	<1	13	110	780	2.75	<10	0.91	1510	19	0.01	16	1040	38	15	<20	186	0.09	<10	19	<10	6	77
32	X12557	5.3	1.01	40	30	<5	3.19	1	13	115	2753	3.58	<10	0.69	919	14	0.01	8	1020	44	20	<20	192	0.09	<10	17	<10	4	48
33	X12558	4.3	1.24	20	80	<5	1.96	1	11	107	2264	3.01	<10	0.82	716	10	0.03	5	1080	32	20	<20	125	0.09	<10	25	<10	5	76
34	X12559	1.7	1.08	15	105	<5	3.29	2	10	90	866	2.98	<10	0.62	1058	14	0.03	8	1150	36	35	<20	270	0.06	<10	28	<10	5	80
35	X12560	<0.2	0.16	35	<5	<5	>10	<1	2	5	5	0.10	<10	1.92	27	<1	<0.01	<1	60	12	10	<20	6718	0.03	<10	6	<10	<1	<1
QC DATA:																													
Repeat:																													
1	X12526	10.8	0.56	20	25	<5	1.97	1	11	96	2078	3.72	<10	0.22	974	17	0.01	6	990	88	5	<20	109	0.03	<10	12	<10	2	59
10	X12535	8.7	0.72	40	30	<5	1.49	6	10	111	1767	3.59	<10	0.35	722	15	0.01	5	1100	266	10	<20	76	0.03	<10	11	<10	3	268
19	X12544	5.0	1.15	40	30	<5	1.84	1	10	96	1337	3.49	<10	0.90	1196	18	0.01	6	1150	38	25	<20	83	0.04	<10	17	<10	5	96
Resplit:																													
1	X12526	10.9	0.57	30	25	<5	2.04	2	12	102	1947	3.75	<10	0.26	943	16	<0.01	7	1070	92	10	<20	111	0.04	<10	12	<10	3	55
Standard:																													
PB113A		11.0	0.25	45	55	<5	1.62	41	3	6	2312	1.10	<10	0.12	1489	60	0.02	5	100	5572	20	<20	81	<0.01	<10	10	<10	<1	7080

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5729S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5732

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07237
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X14386	0.53	0.015
2	X14387	0.43	0.013
3	X14388	0.44	0.013
4	X14389	0.36	0.010
5	X14390	0.52	0.015
6	X14391	0.70	0.020
7	X14392	0.30	0.009
8	X14393	0.71	0.021
9	X14394	0.36	0.010
10	X14395	0.29	0.008
11	X14396	0.42	0.012
12	X14397	0.51	0.015
13	X14398	0.79	0.023
14	X14399	0.46	0.013
15	X14400	0.43	0.013
16	X14401	0.27	0.008
17	X14402	0.35	0.010
18	X14403	0.40	0.012
19	X14404	0.41	0.012
20	X14405	0.87	0.025
21	X14406	0.48	0.014
22	X14407	0.40	0.012
23	X14408	0.40	0.012
24	X14409	0.56	0.016
25	X14410	0.42	0.012
26	X14411	0.22	0.006
27	X14412	1.62	0.047
28	X14413	0.31	0.009

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5732 4-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	X14414	0.46	0.013
30	X14415	0.34	0.010
31	X14416	0.25	0.007
32	X14417	0.24	0.007
33	X14418	0.29	0.008
34	X14419	0.48	0.014
35	X14420	0.32	0.009
QC DATA:			
Repeat:			
1	X14386	0.57	0.017
6	X14391	0.66	0.019
10	X14395	0.28	0.008
13	X14398	0.80	0.023
19	X14404	0.41	0.012
20	X14405	0.87	0.025
34	X14419	0.49	0.014
Resplits:			
1	X14386	0.67	0.020
Standard:			
OXK48		3.52	0.103

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

4-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5732

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07237
Submitted by: Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X14386	2.2	1.43	20	30	<5	2.97	<1	15	60	1815	3.83	<10	1.03	805	92	0.03	5	1500	82	20	<20	273	0.11	<10	68	<10	3	107
2	X14387	2.1	1.40	<5	50	<5	2.37	1	15	100	1653	4.24	<10	1.08	842	51	0.04	7	1420	48	20	<20	160	0.10	<10	76	<10	3	84
3	X14388	1.6	1.44	15	65	<5	4.70	1	15	55	1342	3.82	<10	1.04	1250	172	0.03	4	1530	52	10	<20	283	0.11	<10	65	<10	4	91
4	X14389	1.5	1.40	15	40	<5	3.59	2	14	75	1128	3.94	<10	0.99	1107	63	0.03	8	1560	36	30	<20	244	0.10	<10	64	<10	4	89
5	X14390	2.0	1.24	75	30	<5	4.24	<1	16	52	1315	2.99	<10	0.69	1085	47	0.01	5	1760	34	20	<20	176	0.08	<10	30	<10	4	61
6	X14391	2.4	1.42	45	40	<5	4.07	<1	14	63	1530	3.34	<10	0.91	1092	57	0.02	3	1600	52	<5	<20	201	0.11	<10	52	<10	3	89
7	X14392	1.1	1.39	10	50	<5	3.52	2	16	59	1124	4.63	<10	1.18	971	40	0.04	7	1600	42	20	<20	301	0.13	<10	110	<10	<1	97
8	X14393	2.7	1.55	25	35	<5	2.36	2	16	63	3717	4.00	<10	1.40	850	148	0.03	7	1700	56	25	<20	141	0.09	<10	90	<10	3	78
9	X14394	1.2	1.48	25	60	<5	3.61	2	18	50	1297	4.42	<10	1.17	1102	74	0.03	8	1730	42	30	<20	244	0.10	<10	72	<10	5	85
10	X14395	0.9	1.48	15	45	<5	4.46	2	16	59	1136	4.16	<10	1.11	1172	67	0.03	8	1680	40	25	<20	284	0.10	<10	70	<10	5	78
11	X14396	2.0	1.30	15	35	<5	5.52	2	15	59	2295	4.04	<10	1.02	1340	47	0.03	7	1570	40	25	<20	374	0.09	<10	83	<10	8	78
12	X14397	3.3	1.51	25	35	<5	2.43	<1	18	80	2229	4.60	<10	1.15	946	185	0.03	7	1690	134	20	<20	191	0.12	<10	96	<10	2	116
13	X14398	4.5	1.16	10	25	<5	2.43	2	19	103	3766	5.39	<10	0.96	756	82	0.04	9	1340	50	20	<20	242	0.11	<10	113	<10	<1	99
14	X14399	1.5	1.27	10	35	<5	3.05	2	17	73	1637	4.92	<10	1.10	735	54	0.05	8	1670	40	25	<20	392	0.12	<10	131	<10	1	89
15	X14400	1.6	1.26	20	25	<5	3.73	2	17	75	1470	4.37	<10	1.02	943	51	0.03	7	1450	48	20	<20	281	0.10	<10	102	<10	1	91
16	X14401	1.4	1.29	15	40	<5	4.00	1	15	72	1159	4.00	<10	0.98	1053	37	0.04	6	1600	44	15	<20	240	0.10	<10	88	<10	2	94
17	X14402	1.5	1.28	15	30	<5	3.24	2	16	76	1160	4.57	<10	1.08	903	43	0.04	7	1530	40	25	<20	273	0.11	<10	118	<10	<1	102
18	X14403	1.3	1.18	20	40	<5	3.21	2	17	96	1282	4.24	<10	1.00	745	48	0.04	7	1410	40	15	<20	327	0.10	<10	111	<10	<1	78
19	X14404	1.7	1.45	20	35	<5	3.83	1	19	69	1554	5.45	<10	1.26	1063	46	0.04	7	1560	50	20	<20	320	0.13	<10	139	<10	<1	114
20	X14405	1.9	1.53	25	35	<5	2.64	1	19	92	2112	5.22	<10	1.32	799	55	0.04	9	1610	52	20	<20	290	0.12	<10	116	<10	<1	92
21	X14406	1.7	1.48	25	25	<5	2.00	2	16	85	1847	4.67	<10	1.28	770	60	0.05	7	1580	48	20	<20	194	0.10	<10	113	<10	<1	82
22	X14407	1.3	1.42	25	40	<5	2.23	3	18	79	1489	4.59	<10	1.16	725	58	0.04	11	1640	46	40	<20	169	0.08	<10	93	<10	<1	82
23	X14408	2.2	1.38	90	25	<5	3.63	<1	17	60	1121	3.97	<10	1.00	915	73	0.02	7	1610	44	25	<20	264	0.09	<10	53	<10	2	80
24	X14409	3.1	0.89	85	15	<5	2.83	<1	17	114	1478	4.80	<10	0.47	576	85	0.02	9	1470	50	15	<20	198	0.08	<10	34	<10	3	45
25	X14410	2.3	1.24	45	30	<5	1.83	1	18	68	1669	3.93	<10	0.85	636	126	0.03	8	1820	52	20	<20	71	0.08	<10	49	<10	4	61

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X14411	0.8	1.55	30	45	<5	2.22	<1	19	76	1088	4.21	<10	1.27	701	74	0.04	6	1800	52	25	<20	172	0.10	<10	78	<10	<1	82
27	X14412	<0.2	0.87	2350	85	30	0.93	<1	34	31	64	5.03	<10	2.01	759	5	0.18	125	1090	40	30	<20	84	0.11	<10	27	<10	6	59
28	X14413	1.2	1.37	35	35	<5	2.50	<1	17	67	1396	3.94	<10	1.10	693	56	0.04	6	1660	54	20	<20	218	0.11	<10	77	<10	1	78
29	X14414	2.0	1.51	35	35	<5	1.78	1	17	94	2257	4.65	<10	1.32	755	65	0.04	8	1580	56	25	<20	177	0.10	<10	107	<10	<1	85
30	X14415	1.1	1.40	30	55	<5	1.93	<1	17	69	1218	4.40	<10	1.19	691	54	0.04	7	1700	46	20	<20	154	0.10	<10	105	<10	<1	86
31	X14416	1.0	1.39	30	95	<5	2.31	<1	17	60	1165	4.37	<10	1.11	735	77	0.04	6	1860	154	15	<20	190	0.11	<10	97	<10	2	91
32	X14417	1.2	1.51	45	75	<5	2.50	<1	15	58	993	4.47	<10	1.20	1154	44	0.04	7	1750	62	20	<20	136	0.10	<10	91	<10	1	114
33	X14418	0.9	1.39	25	90	<5	2.87	3	15	85	922	4.41	<10	1.13	950	47	0.04	10	1600	50	40	<20	200	0.08	<10	93	<10	<1	95
34	X14419	2.5	1.43	120	25	<5	3.19	<1	17	60	1514	3.88	<10	1.04	1121	60	0.02	7	1710	76	20	<20	100	0.08	<10	46	<10	3	93
35	X14420	1.8	1.59	35	40	<5	2.84	<1	17	89	1630	4.12	<10	1.31	1094	54	0.04	8	1750	68	30	<20	121	0.09	<10	77	<10	2	102
QC DATA:																													
Repeat:																													
1	X14386	2.4	1.40	25	25	<5	3.02	1	15	60	1799	3.89	<10	1.02	818	96	0.03	6	1580	86	15	<20	271	0.10	<10	66	<10	2	110
10	X14395	0.9	1.39	15	40	<5	4.49	1	16	55	1125	4.18	<10	1.08	1179	62	0.03	7	1730	44	15	<20	266	0.10	<10	65	<10	5	81
19	X14404	1.8	1.43	25	35	<5	3.83	2	19	67	1539	5.43	<10	1.24	1062	47	0.04	8	1570	52	25	<20	318	0.12	<10	135	<10	1	115
Resplit:																													
1	X14386	2.5	1.32	25	30	<5	3.20	1	16	59	1813	4.10	<10	0.99	836	94	0.02	5	1570	92	25	<20	288	0.10	<10	66	<10	2	108
Standard:																													
PB113A		11.6	0.26	45	55	<5	1.67	38	3	6	2305	1.13	<10	0.11	1528	61	0.02	4	100	5618	20	<20	88	0.02	<10	10	<10	<1	7060

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5729S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5733

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07221
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	X10707	0.74	0.022		
2	X10708	0.85	0.025		
3	X10709	0.75	0.022		
4	X10710	0.90	0.026		
5	X10711	0.75	0.022		
6	X10712	0.81	0.024		
7	X10713	1.83	0.053		
8	X10714	0.71	0.021		
9	X10715	<0.03	<0.001		
10	X10716	0.82	0.024		
11	X10717	1.00	0.029		
12	X10718	0.69	0.020		
13	X10719	0.59	0.017		
14	X10720	0.65	0.019		
15	X10721	0.74	0.022		
16	X10722	0.85	0.025		
17	X10723	0.49	0.014		
18	X10724	0.50	0.015		
19	X10725	0.43	0.013	32.3	0.942
20	X10726	0.42	0.012		
21	X10727	0.71	0.021		
22	X10728	0.48	0.014		
23	X10729	0.49	0.014		
24	X10730	0.41	0.012		
25	X10731	0.60	0.017		
26	X10732	0.58	0.017		
27	X10733	0.49	0.014		
28	X10734	0.73	0.021		
29	X10735	0.53	0.015		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5733 4-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
30	X10736	0.35	0.010		
31	X10737	0.36	0.010		
32	X10738	0.54	0.016		
33	X10739	0.55	0.016		
34	X10740	0.62	0.018		
35	X10741	0.43	0.013		
QC DATA:					
Repeat:					
1	X10707	0.84	0.024		
4	X10710	0.87	0.025		
5	X10711	0.83	0.024		
8	X10714	0.68	0.020		
10	X10716	0.93	0.027		
11	X10717	0.97	0.028		
19	X10725	0.47	0.014		
Resplits:					
1	X10707	0.81	0.024		
Standard:					
OXK48		3.52	0.103		
Pb113				23.0	0.671

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

4-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5733

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07221
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10707	4.4	0.68	<5	45	<5	0.21	3	12	118	2456	6.41	<10	0.42	307	27	0.01	8	430	28	15	<20	19	0.01	<10	16	<10	<1	64
2	X10708	4.2	0.50	<5	40	<5	0.22	2	11	128	2003	5.52	<10	0.17	231	43	0.01	5	620	56	<5	<20	55	0.02	<10	11	<10	<1	53
3	X10709	3.7	0.71	20	45	<5	0.19	3	11	127	2007	6.04	<10	0.34	279	18	0.01	8	700	30	15	<20	20	0.02	<10	15	<10	<1	52
4	X10710	3.6	0.52	<5	40	<5	0.21	2	13	119	3026	5.54	<10	0.23	175	20	0.01	6	590	30	<5	<20	19	0.01	<10	13	<10	<1	36
5	X10711	3.2	0.66	30	35	<5	0.32	2	11	135	1543	5.05	<10	0.40	249	26	0.01	6	720	40	10	<20	116	0.02	<10	15	<10	<1	65
6	X10712	4.1	0.58	<5	45	<5	0.26	3	12	142	3823	5.19	<10	0.36	232	21	0.02	7	490	38	10	<20	29	0.02	<10	19	<10	<1	125
7	X10713	3.9	1.18	35	45	<5	0.98	2	22	62	8576	3.99	10	0.61	192	600	0.04	62	200	74	25	<20	59	0.02	<10	44	<10	5	74
8	X10714	2.9	0.54	<5	35	<5	0.45	4	10	120	3222	4.93	<10	0.39	400	61	0.02	12	550	26	30	<20	29	<0.01	<10	20	<10	<1	37
9	X10715	<0.2	0.03	20	<5	<5	>10	<1	2	4	4	0.02	<10	1.76	19	<1	<0.01	<1	30	8	<5	<20	6331	0.02	<10	3	<10	<1	<1
10	X10716	3.7	0.45	10	50	<5	0.29	2	14	138	2927	5.59	<10	0.12	102	54	0.01	7	1030	32	5	<20	28	0.02	<10	12	<10	2	29
11	X10717	3.1	0.61	45	50	<5	0.64	2	11	145	2975	5.27	<10	0.39	392	25	0.02	7	550	32	15	<20	59	0.01	<10	15	<10	<1	40
12	X10718	3.1	0.46	<5	40	<5	0.53	2	14	137	2678	6.46	<10	0.17	159	14	0.02	8	640	26	5	<20	153	0.01	<10	14	<10	<1	23
13	X10719	1.8	1.17	10	50	<5	0.84	1	11	128	1605	4.82	<10	0.95	761	12	0.02	5	700	34	10	<20	69	0.02	<10	23	<10	1	60
14	X10720	1.5	1.80	10	55	<5	1.59	2	10	111	1301	4.85	<10	1.61	1183	14	0.02	5	800	48	20	<20	135	0.03	<10	29	<10	2	90
15	X10721	2.6	0.66	5	45	<5	1.26	2	16	134	1657	5.63	<10	0.55	919	13	0.01	7	630	30	10	<20	94	0.03	<10	15	<10	3	31
16	X10722	5.6	0.48	5	40	<5	0.49	2	14	136	2869	4.86	<10	0.37	525	11	0.01	6	490	20	5	<20	26	0.01	<10	14	<10	<1	39
17	X10723	8.9	0.38	<5	40	<5	1.53	4	11	96	2325	5.59	<10	0.69	1544	12	0.01	6	690	38	15	<20	54	0.03	<10	10	<10	1	83
18	X10724	24.4	0.33	75	35	<5	2.55	6	11	121	1753	4.57	<10	0.98	2438	10	0.01	5	730	132	45	<20	100	0.04	<10	9	<10	3	224
19	X10725	>30	0.33	160	45	<5	4.58	9	13	113	2027	4.25	<10	1.99	4918	9	0.01	6	650	352	105	<20	179	0.05	<10	10	<10	7	244
20	X10726	12.6	0.50	15	30	<5	2.38	12	9	88	1657	3.98	<10	0.88	1952	17	0.02	2	850	1036	<5	<20	138	0.03	<10	11	<10	5	625
21	X10727	6.5	1.34	10	45	<5	1.37	2	11	100	1954	3.81	<10	1.37	1319	15	0.01	4	930	56	15	<20	96	0.02	<10	22	<10	3	132
22	X10728	4.8	1.23	5	40	<5	1.16	2	10	93	1249	4.02	<10	1.13	1364	18	0.01	9	950	46	35	<20	88	0.02	<10	20	<10	4	119
23	X10729	15.7	0.66	10	35	<5	1.62	9	10	86	2021	4.32	<10	0.80	1770	17	0.02	4	900	208	15	<20	85	0.03	<10	15	<10	4	317
24	X10730	6.8	0.84	30	45	<5	0.99	2	11	91	1319	4.57	<10	0.73	941	16	0.01	5	1040	40	15	<20	61	0.02	<10	16	<10	3	65
25	X10731	6.1	0.55	30	40	<5	1.19	2	12	96	1817	5.10	<10	0.49	975	17	0.02	5	890	32	15	<20	65	0.02	<10	13	<10	3	33

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10732	5.2	0.59	20	35	<5	2.81	2	11	82	1552	4.30	<10	0.55	1807	16	0.01	3	840	30	5	<20	154	0.03	<10	13	<10	2	45
27	X10733	3.3	0.66	20	40	<5	2.84	2	12	67	877	4.98	<10	0.59	1635	15	0.01	5	960	64	10	<20	160	0.03	<10	13	<10	3	65
28	X10734	6.5	0.61	15	40	<5	1.68	2	13	102	2662	3.85	<10	0.58	1226	12	0.02	5	820	34	15	<20	101	0.02	<10	15	<10	4	40
29	X10735	4.8	1.05	15	45	<5	2.08	3	12	91	2309	3.89	<10	0.91	1398	15	0.01	5	850	54	20	<20	142	0.02	<10	18	<10	3	123
30	X10736	2.2	1.09	<5	45	<5	2.71	1	9	82	1201	3.03	<10	0.76	1401	18	0.01	4	1010	36	15	<20	221	0.02	<10	17	<10	3	81
31	X10737	2.1	1.16	5	45	<5	1.98	2	10	87	1514	3.34	<10	0.86	1116	16	0.01	4	1010	38	15	<20	166	0.02	<10	18	<10	4	75
32	X10738	3.0	1.18	20	40	<5	1.91	<1	9	73	2095	3.41	<10	0.87	964	11	0.01	1	930	34	<5	<20	158	0.03	<10	18	<10	3	80
33	X10739	2.8	1.25	<5	50	<5	2.39	3	11	79	1972	3.89	<10	0.91	1069	19	0.01	8	980	36	30	<20	203	0.02	<10	23	<10	5	68
34	X10740	4.4	0.97	15	50	<5	2.24	1	11	79	2274	3.48	<10	0.63	1089	17	0.01	4	870	30	10	<20	179	0.02	<10	16	<10	4	50
35	X10741	2.8	0.92	20	50	<5	3.68	<1	9	68	1025	2.93	<10	0.72	2139	14	0.01	2	760	28	10	<20	216	0.03	<10	13	<10	4	70
QC DATA:																													
Repeat:																													
1	X10707	4.4	0.64	5	50	<5	0.22	3	13	112	2473	6.39	<10	0.41	307	27	0.01	6	450	30	15	<20	21	0.02	<10	15	<10	<1	63
10	X10716	3.7	0.38	<5	50	<5	0.29	1	14	128	2923	5.58	<10	0.10	104	54	0.01	5	1070	30	<5	<20	26	0.02	<10	10	<10	1	28
19	X10725	>30	0.33	155	45	<5	4.65	9	13	107	2013	4.25	<10	1.97	4899	10	0.01	6	630	356	110	<20	181	0.05	<10	8	<10	8	240
Resplit:																													
1	X10707	4.3	0.69	5	40	<5	0.22	4	11	124	2482	6.47	<10	0.43	310	24	0.01	10	480	28	20	<20	19	0.01	<10	16	<10	<1	63
Standard:																													
PB113A		11.0	0.27	55	65	<5	1.70	35	3	6	2184	1.00	<10	0.10	1390	68	0.02	3	90	5500	15	<20	91	0.01	<10	8	<10	<1	6911

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5733S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5734

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

4-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07232
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X12561	0.24	0.007
2	X12562	0.24	0.007
3	X12563	0.14	0.004
4	X12564	0.38	0.011
5	X12565	0.50	0.015
6	X12566	0.61	0.018
7	X12567	0.34	0.010
8	X12568	0.30	0.009
9	X12569	0.42	0.012
10	X12570	0.43	0.013
11	X12571	0.27	0.008
12	X12572	0.31	0.009
13	X12573	0.52	0.015
14	X12574	0.40	0.012
15	X12575	0.33	0.010
16	X12576	0.30	0.009
17	X12577	0.49	0.014
18	X12578	<0.03	<0.001
19	X12579	0.28	0.008
20	X12580	0.51	0.015
21	X12581	0.16	0.005
22	X12582	0.34	0.010
23	X12583	0.17	0.005
24	X12584	0.26	0.008
25	X12585	0.17	0.005
26	X12586	0.29	0.008
27	X12587	0.28	0.008
28	X12588	0.33	0.010
29	X12589	0.43	0.013

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5734 4-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X12590	0.46	0.013
31	X12591	0.20	0.006
32	X12592	0.96	0.028
33	X12593	0.30	0.009
34	X12594	0.28	0.008
35	X12595	0.58	0.017

QC DATA:

Repeat:

1	X12561	0.28	0.008
6	X12566	0.62	0.018
10	X12570	0.47	0.014
20	X12580	0.57	0.017

Resplits:

1	X12561	0.26	0.008

Standard:

OXK48		3.58	0.104

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

4-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5734

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07232
Submitted by: Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X12561	0.9	0.77	5	95	<5	2.23	2	9	59	637	2.80	<10	0.51	738	18	0.03	4	1070	30	15	<20	152	0.06	<10	27	<10	6	71
2	X12562	0.8	0.65	<5	145	<5	2.41	2	8	74	980	2.70	<10	0.37	666	21	0.03	5	950	32	10	<20	192	0.07	<10	30	<10	1	51
3	X12563	1.0	0.67	<5	135	<5	3.20	<1	9	74	1058	2.19	<10	0.41	879	19	0.02	3	850	32	10	<20	275	0.08	<10	22	<10	4	58
4	X12564	0.8	0.84	<5	170	<5	1.94	1	8	71	1062	3.35	<10	0.58	684	10	0.04	6	930	28	10	<20	165	0.09	<10	45	<10	2	70
5	X12565	1.4	0.67	10	50	<5	1.91	1	11	86	1482	2.14	<10	0.42	553	53	0.02	4	960	82	10	<20	88	0.07	<10	15	<10	2	85
6	X12566	2.0	0.64	<5	55	<5	2.55	2	9	82	2315	2.49	<10	0.42	653	16	0.02	5	830	26	15	<20	121	0.06	<10	24	<10	2	61
7	X12567	0.8	0.59	<5	260	<5	2.55	<1	7	62	1046	2.37	<10	0.36	610	13	0.02	3	970	22	5	<20	159	0.08	<10	33	<10	2	51
8	X12568	0.8	0.73	<5	155	<5	2.99	<1	8	67	982	2.26	<10	0.46	665	13	0.02	5	920	26	15	<20	166	0.07	<10	23	<10	2	54
9	X12569	1.0	0.86	<5	80	<5	1.23	1	8	95	1518	2.39	<10	0.65	511	10	0.03	4	980	22	15	<20	74	0.07	<10	25	<10	2	55
10	X12570	1.0	0.78	<5	85	<5	1.78	1	9	74	1623	2.40	<10	0.55	540	27	0.03	3	960	24	10	<20	107	0.08	<10	26	<10	3	47
11	X12571	0.8	0.75	<5	65	<5	2.27	1	10	54	870	2.98	<10	0.52	639	57	0.03	4	950	28	10	<20	157	0.09	<10	29	<10	1	52
12	X12572	1.3	0.72	<5	90	<5	2.40	1	11	130	1254	3.48	<10	0.47	677	24	0.03	6	720	28	10	<20	166	0.09	<10	37	<10	2	57
13	X12573	1.1	0.77	<5	180	<5	3.00	1	8	73	926	3.05	<10	0.52	778	29	0.02	5	1000	22	15	<20	176	0.08	<10	29	<10	2	64
14	X12574	1.6	0.69	5	50	<5	1.48	1	9	99	1568	2.55	<10	0.46	524	31	0.02	4	890	36	10	<20	99	0.06	<10	21	<10	3	57
15	X12575	1.2	0.65	10	85	<5	2.60	1	7	69	757	2.10	<10	0.40	777	39	0.02	5	980	30	15	<20	128	0.05	<10	17	<10	5	56
16	X12576	1.6	0.63	10	65	<5	1.91	<1	9	98	1024	1.92	<10	0.34	551	53	0.01	5	1000	24	10	<20	117	0.06	<10	14	<10	3	46
17	X12577	6.1	0.47	10	30	<5	1.59	2	12	90	2947	2.17	<10	0.23	431	23	0.01	6	850	70	15	<20	113	0.03	<10	8	<10	4	61
18	X12578	<0.2	0.03	15	<5	<5	>10	<1	2	4	4	0.03	<10	2.07	28	<1	<0.01	<1	70	6	25	<20	6808	0.02	<10	3	<10	<1	<1
19	X12579	3.2	1.12	20	35	<5	0.95	3	20	56	2649	3.34	10	0.62	186	199	0.03	11	500	68	20	<20	51	0.06	<10	46	<10	3	271
20	X12580	3.4	0.71	5	50	<5	3.08	1	10	88	2031	1.94	<10	0.51	791	158	0.02	5	800	30	10	<20	216	0.06	<10	16	<10	5	52
21	X12581	0.8	1.18	<5	75	<5	3.00	1	13	45	577	2.44	<10	0.98	768	58	0.02	15	840	32	20	<20	135	0.07	<10	25	<10	3	47
22	X12582	0.9	0.89	10	75	<5	2.57	1	12	92	848	2.35	<10	0.71	695	143	0.02	16	800	32	15	<20	144	0.08	<10	21	<10	5	47
23	X12583	1.0	0.68	10	80	<5	1.65	<1	10	97	730	2.22	<10	0.37	451	35	0.02	4	970	26	5	<20	106	0.08	<10	22	<10	4	39
24	X12584	1.2	0.75	<5	60	<5	2.22	1	9	80	670	2.43	<10	0.50	616	36	0.02	4	1010	48	15	<20	122	0.06	<10	24	<10	3	55
25	X12585	0.9	0.76	<5	105	<5	2.29	1	8	53	537	2.38	<10	0.47	642	55	0.02	4	990	24	10	<20	99	0.05	<10	28	<10	2	45

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X12586	1.3	0.69	15	60	<5	2.47	<1	10	80	802	2.27	<10	0.42	674	45	0.02	4	960	28	10	<20	102	0.06	<10	18	<10	4	45
27	X12587	1.1	0.63	10	50	<5	2.32	<1	10	74	663	1.95	<10	0.38	630	51	0.01	3	1010	28	10	<20	98	0.06	<10	15	<10	2	48
28	X12588	1.3	0.72	15	55	<5	3.46	<1	12	63	533	2.40	<10	0.45	918	19	0.02	3	1000	60	15	<20	140	0.06	<10	17	<10	4	74
29	X12589	2.2	0.76	40	50	<5	3.99	2	11	100	957	2.95	<10	0.55	1154	33	0.01	7	950	36	25	<20	135	0.06	<10	17	<10	4	55
30	X12590	3.7	0.75	10	50	<5	3.29	2	10	81	2032	2.46	<10	0.50	928	95	0.01	5	850	40	15	<20	111	0.06	<10	14	<10	5	57
31	X12591	1.1	0.81	5	100	<5	3.44	1	7	81	825	1.76	<10	0.56	911	50	0.01	4	880	28	10	<20	126	0.06	<10	13	<10	5	50
32	X12592	1.6	0.48	30	40	<5	3.08	<1	10	86	550	2.15	<10	0.24	783	62	0.01	4	840	36	10	<20	100	0.06	<10	8	<10	4	37
33	X12593	4.1	0.69	15	50	<5	3.65	1	8	74	968	2.13	<10	0.45	1001	194	0.02	3	930	40	10	<20	110	0.07	<10	13	<10	4	75
34	X12594	4.5	0.67	5	50	<5	2.73	<1	8	107	1003	2.37	<10	0.42	826	73	0.02	4	840	38	5	<20	106	0.07	<10	16	<10	2	55
35	X12595	1.4	0.83	<5	115	<5	2.15	<1	9	86	1749	2.82	<10	0.54	663	100	0.03	4	790	30	5	<20	158	0.08	<10	31	<10	2	56
QC DATA:																													
Repeat:																													
1	X12561	0.8	0.80	<5	85	<5	2.26	1	8	59	702	2.83	<10	0.54	765	17	0.03	4	990	26	10	<20	167	0.08	<10	27	<10	3	69
10	X12570	1.2	0.76	<5	75	<5	1.77	2	9	72	1626	2.40	<10	0.55	543	28	0.03	5	960	24	20	<20	103	0.06	<10	25	<10	2	47
Resplit:																													
1	X12561	0.9	0.85	<5	90	<5	2.23	2	9	62	651	3.09	<10	0.57	747	20	0.03	5	1030	28	15	<20	198	0.08	<10	31	<10	3	71
Standard:																													
PB113A		11.0	0.25	45	50	<5	1.64	38	3	6	2295	1.00	<10	0.11	1474	65	0.01	3	90	5542	25	<20	89	0.02	<10	8	<10	<1	6924

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5733S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5735

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

6-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07231
Submitted by: Tim Dodd

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X14211	0.65	0.019
2	X14212	0.22	0.006
3	X14213	0.18	0.005
4	X14214	0.29	0.008
5	X14215	1.25	0.036
6	X14216	0.36	0.010
7	X14217	0.21	0.006
8	X14218	0.23	0.007
9	X14219	0.25	0.007
10	X14220	0.24	0.007
11	X14221	0.23	0.007
12	X14222	0.10	0.003
13	X14223	0.20	0.006
14	X14224	0.23	0.007
15	X14225	0.15	0.004
16	X14226	0.10	0.003
17	X14227	0.23	0.007
18	X14228	0.10	0.003
19	X14229	0.13	0.004
20	X14230	<0.03	<0.001
21	X14231	0.16	0.005
22	X14232	0.17	0.005
23	X14233	0.09	0.003
24	X14234	0.09	0.003
25	X14235	0.15	0.004
26	X14236	0.10	0.003
27	X14237	0.24	0.007
28	X14238	0.16	0.005
29	X14239	0.07	0.002

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5735 6-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X14240	0.29	0.008
31	X14241	0.14	0.004
32	X14242	0.15	0.004
33	X14243	0.12	0.003
34	X14244	0.13	0.004
35	X14245	0.16	0.005

QC DATA:

Repeat:

1	X14211	0.69	0.020
10	X14220	0.22	0.006
19	X14229	0.13	0.004


Resplits:

1	X14211	0.60	0.017

Standard:

SN26		8.53	0.249

AU: 30g FA/AA-Finish



ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

5-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5735

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07231
Submitted by: Tim Dodd

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X14211	4.0	0.87	5	45	<5	0.83	2	15	101	507	4.66	<10	0.64	326	122	0.02	5	1360	36	10	<20	25	0.03	<10	15	<10	2	41
2	X14212	2.4	0.65	<5	50	<5	1.21	1	16	77	407	4.04	<10	0.43	411	87	0.02	5	1520	30	<5	<20	41	0.02	<10	11	<10	4	29
3	X14213	2.7	0.46	<5	65	<5	1.16	1	14	67	528	4.50	<10	0.21	370	61	0.02	5	1420	32	<5	<20	44	0.02	<10	7	<10	2	15
4	X14214	3.0	0.64	<5	55	<5	0.96	2	18	93	421	4.97	<10	0.36	329	94	0.02	6	1440	48	10	<20	28	0.02	<10	10	<10	<1	23
5	X14215	8.5	0.50	10	55	<5	2.02	2	14	89	666	3.94	<10	0.24	787	40	0.02	6	1280	26	15	<20	43	0.03	<10	8	<10	4	46
6	X14216	2.4	0.82	<5	65	<5	1.33	<1	16	67	557	4.48	<10	0.61	495	27	0.02	4	1430	28	<5	<20	47	0.03	<10	13	<10	5	34
7	X14217	1.7	1.14	<5	60	<5	1.86	<1	16	85	435	5.13	<10	0.93	775	14	0.02	5	1370	30	10	<20	47	0.03	<10	18	<10	6	44
8	X14218	1.3	1.15	<5	55	<5	1.59	1	14	67	521	4.37	<10	0.99	705	74	0.03	6	1520	32	10	<20	42	0.03	<10	20	<10	5	47
9	X14219	1.5	0.79	<5	55	<5	0.64	2	16	80	406	5.35	<10	0.59	237	65	0.03	7	1510	32	5	<20	35	0.03	<10	14	<10	2	29
10	X14220	0.8	0.96	<5	50	<5	0.60	1	17	74	404	5.21	<10	0.76	242	25	0.03	6	1480	30	<5	<20	21	0.03	<10	16	<10	2	23
11	X14221	0.4	1.30	<5	55	<5	0.43	1	16	72	369	4.29	<10	1.19	260	43	0.04	8	1560	34	15	<20	26	0.02	<10	27	<10	2	24
12	X14222	0.6	0.53	<5	50	10	0.40	<1	18	77	237	4.78	<10	0.27	70	28	0.05	6	1590	20	<5	<20	25	0.02	<10	9	<10	1	8
13	X14223	0.6	0.88	<5	45	<5	0.38	1	19	83	290	5.27	<10	0.68	146	28	0.04	6	1460	24	<5	<20	22	0.02	<10	14	<10	1	16
14	X14224	0.7	0.75	<5	60	5	0.45	1	16	79	240	5.07	<10	0.54	144	28	0.04	6	1510	28	<5	<20	38	0.03	<10	12	<10	3	11
15	X14225	0.6	0.87	<5	55	5	1.39	2	19	85	233	5.15	<10	0.70	446	51	0.04	6	1440	38	10	<20	55	0.03	<10	14	<10	4	23
16	X14226	1.0	0.67	<5	50	5	0.67	2	18	83	190	4.51	<10	0.46	198	125	0.05	6	1430	26	10	<20	37	0.02	<10	10	<10	<1	14
17	X14227	0.2	1.12	<5	50	<5	0.52	<1	18	73	245	4.24	<10	0.99	247	67	0.03	6	1530	30	10	<20	28	0.02	<10	18	<10	3	19
18	X14228	0.7	0.72	<5	55	20	3.25	<1	14	55	119	3.85	<10	0.74	663	3	0.01	4	1450	30	<5	<20	196	0.03	<10	30	<10	4	34
19	X14229	0.7	0.77	<5	50	25	2.77	2	18	60	153	4.86	<10	0.80	583	9	0.01	5	1480	56	<5	<20	170	0.03	<10	31	<10	4	40
20	X14230	<0.2	0.02	15	<5	10	>10	<1	2	2	2	0.03	<10	1.94	26	<1	<0.01	<1	40	8	15	<20	6208	<0.01	<10	2	<10	<1	<1
21	X14231	0.6	0.89	<5	55	<5	2.66	2	15	50	222	4.02	<10	1.03	475	5	0.02	6	1500	32	10	<20	170	0.02	<10	41	<10	3	42
22	X14232	0.5	0.84	<5	75	10	2.26	2	14	50	170	4.07	<10	0.94	418	14	0.01	6	1490	26	15	<20	273	0.02	<10	32	<10	2	40
23	X14233	0.5	0.77	<5	70	<5	2.38	1	16	58	152	3.59	<10	0.84	490	7	<0.01	5	1520	26	<5	<20	275	0.02	<10	35	<10	2	30
24	X14234	0.8	0.70	<5	65	15	2.17	2	19	58	140	4.75	<10	0.70	603	7	<0.01	5	1430	32	<5	<20	128	0.03	<10	27	<10	2	30
25	X14235	1.3	1.09	<5	40	<5	1.23	2	18	67	237	5.80	<10	1.14	567	8	<0.01	8	1490	32	10	<20	53	0.03	<10	38	<10	<1	61

ECO TECH LABORATORY LTD. | ICP CERTIFICATE OF ANALYSIS AS 2007-5735 | Seabridge Gold Inc.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X14236	4.2	0.68	15	45	5	2.32	9	15	65	150	5.02	<10	0.72	944	5	<0.01	5	1630	224	30	<20	131	0.03	<10	25	<10	2	231
27	X14237	1.0	1.08	<5	50	10	2.33	1	14	53	115	4.43	<10	1.25	918	7	<0.01	5	1570	50	5	<20	146	0.03	<10	37	<10	3	84
28	X14238	0.7	0.97	<5	40	35	1.69	1	17	62	148	3.84	<10	1.09	615	6	<0.01	5	1650	32	10	<20	105	0.03	<10	40	<10	3	50
29	X14239	0.9	1.10	<5	55	20	1.90	1	15	56	117	4.18	<10	1.25	890	17	<0.01	5	1600	36	10	<20	123	0.03	<10	41	<10	4	68
30	X14240	3.2	1.12	25	65	<5	1.01	3	22	53	2729	3.60	10	0.68	201	205	0.03	9	440	74	10	<20	63	0.06	<10	47	<10	7	279
31	X14241	0.6	0.74	<5	55	<5	1.10	1	19	77	197	5.07	<10	0.76	519	7	<0.01	6	1440	32	<5	<20	72	0.03	<10	18	<10	1	26
32	X14242	0.7	0.66	<5	45	<5	0.71	2	16	81	256	5.53	<10	0.58	281	8	<0.01	8	1520	22	<5	<20	45	0.03	<10	13	<10	<1	23
33	X14243	0.4	1.02	<5	55	5	1.56	2	16	75	199	4.28	<10	1.10	780	14	0.01	8	1550	38	20	<20	101	0.02	<10	28	<10	5	51
34	X14244	0.4	1.22	<5	50	<5	0.79	1	12	62	231	4.20	<10	1.33	456	7	0.01	5	1740	46	15	<20	53	0.03	<10	35	<10	4	84
35	X14245	0.6	1.46	<5	45	<5	1.56	1	15	60	322	4.13	<10	1.70	729	10	0.01	5	1680	40	15	<20	93	0.03	<10	54	<10	4	71
QC DATA:																													
Repeat:																													
1	X14211	3.9	0.88	10	50	<5	0.83	2	15	102	502	4.65	<10	0.64	326	121	0.02	6	1360	34	10	<20	27	0.03	<10	15	<10	2	38
10	X14220	0.7	0.99	<5	55	<5	0.59	<1	16	75	405	5.17	<10	0.77	244	25	0.03	6	1460	32	<5	<20	24	0.03	<10	16	<10	3	23
19	X14229	0.7	0.81	<5	45	20	2.68	2	18	61	154	4.90	<10	0.84	593	9	0.01	6	1490	50	<5	<20	163	0.03	<10	33	<10	3	41
Resplit:																													
1	X14211	3.7	0.89	5	45	<5	0.82	1	15	90	512	4.90	<10	0.68	320	120	0.02	7	1380	30	10	<20	30	0.03	<10	15	<10	3	38
Standard:																													
PB113A		11.6	0.25	45	60	<5	1.68	38	3	6	2317	1.05	<10	0.11	1424	66	0.02	2	90	5396	20	<20	86	0.03	<10	7	<10	<1	6986

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5735S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5736

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

6-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07223
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10777	0.29	0.008
2	X10778	0.45	0.013
3	X10779	0.44	0.013
4	X10780	0.41	0.012
5	X10781	0.35	0.010
6	X10782	0.22	0.006
7	X10783	0.23	0.007
8	X10784	0.53	0.015
9	X10785	0.19	0.006
10	X10786	0.29	0.008
11	X10787	0.39	0.011
12	X10788	0.51	0.015
13	X10789	0.73	0.021
14	X10790	0.42	0.012
15	X10791	0.41	0.012
16	X10792	0.80	0.023
17	X10793	0.40	0.012
18	X10794	0.44	0.013
19	X10795	0.48	0.014
20	X10796	0.29	0.008
21	X10797	0.60	0.017
22	X10798	0.51	0.015
23	X10799	0.78	0.023
24	X10800	0.68	0.020
25	X10801	0.89	0.026
26	X10802	0.57	0.017
27	X10803	1.05	0.031
28	X10804	0.53	0.015
29	X10805	0.39	0.011

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5736 6-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X10806	<0.03	<0.001
31	X10807	0.48	0.014
32	X10808	1.34	0.039
33	X10809	0.59	0.017
34	X10810	0.52	0.015
35	X10811	0.57	0.017

QC DATA:

Repeat:

1	X10777	0.27	0.008
10	X10786	0.33	0.010
19	X10795	0.52	0.015

Resplits:

1	X10777	0.31	0.009

Standard:

SN26		8.55	0.249

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

5-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 2007-5736

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Phone: 250-573-5700
Fax : 250-573-4557


No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07223
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10777	1.7	0.81	15	65	<5	3.48	1	7	72	893	2.16	<10	0.50	1657	14	0.01	3	1140	24	10	<20	143	0.03	<10	12	<10	7	43
2	X10778	2.0	0.67	25	60	<5	3.31	1	9	60	1121	2.83	<10	0.41	1721	22	0.02	4	1170	22	5	<20	119	0.03	<10	11	<10	5	46
3	X10779	3.4	0.42	25	45	<5	2.22	1	13	75	1898	3.56	<10	0.08	1173	24	0.02	3	1130	20	<5	<20	79	0.03	<10	8	<10	5	18
4	X10780	2.5	0.55	45	50	<5	2.84	2	11	65	1166	3.98	<10	0.27	2136	21	0.01	4	1080	20	<5	<20	107	0.04	<10	11	<10	5	37
5	X10781	3.0	0.60	25	55	<5	2.44	1	13	74	1620	4.52	<10	0.43	2421	19	0.01	3	960	18	5	<20	115	0.05	<10	11	<10	4	47
6	X10782	4.1	0.79	50	55	<5	3.50	2	10	108	1184	3.91	<10	0.68	5062	21	0.02	5	990	20	10	<20	141	0.07	<10	14	<10	5	64
7	X10783	5.5	0.64	25	50	<5	3.25	3	9	67	1766	3.55	<10	0.52	3087	19	0.02	4	1040	22	15	<20	108	0.04	<10	15	<10	5	100
8	X10784	7.0	0.55	20	50	<5	2.44	4	10	107	1958	4.91	<10	0.43	3890	13	0.01	7	640	30	15	<20	123	0.05	<10	18	<10	2	110
9	X10785	3.1	1.16	10	55	<5	2.87	2	11	64	1578	3.56	<10	1.24	2353	22	0.02	3	1080	28	5	<20	116	0.04	<10	21	<10	5	98
10	X10786	4.1	0.98	30	50	<5	2.02	2	10	84	2064	3.99	<10	1.02	1748	19	0.02	3	1010	28	10	<20	80	0.04	<10	18	<10	5	74
11	X10787	7.4	1.16	10	55	<5	2.24	2	14	91	3458	4.39	<10	1.54	2193	17	0.02	5	900	32	25	<20	94	0.04	<10	21	<10	4	95
12	X10788	4.9	0.84	15	55	<5	2.60	2	9	76	1953	3.91	<10	1.00	2019	16	0.02	3	1070	26	10	<20	96	0.04	<10	15	<10	5	67
13	X10789	10.1	0.47	55	50	<5	2.20	3	12	146	4124	4.51	<10	0.70	2026	15	0.01	5	290	22	30	<20	101	0.04	<10	13	<10	3	58
14	X10790	5.5	0.96	35	60	<5	1.92	3	15	118	2106	5.07	<10	1.39	2241	16	0.02	5	1110	40	20	<20	93	0.05	<10	18	<10	6	91
15	X10791	6.9	0.74	20	45	<5	1.37	2	11	130	2697	4.72	<10	0.91	1404	12	0.01	5	620	24	<5	<20	73	0.03	<10	18	<10	3	58
16	X10792	9.6	1.09	30	60	<5	1.29	2	13	172	1938	4.97	<10	1.22	1297	13	0.01	8	950	32	10	<20	86	0.03	<10	28	<10	3	92
17	X10793	7.3	0.70	20	50	<5	1.27	2	20	122	1573	5.52	<10	0.82	1294	13	0.01	5	650	42	5	<20	84	0.04	<10	16	<10	3	74
18	X10794	3.3	1.02	<5	60	<5	2.07	2	13	161	1246	4.59	<10	1.39	2220	12	0.01	7	720	30	20	<20	110	0.04	<10	20	<10	4	74
19	X10795	3.0	1.10	<5	60	<5	1.80	1	12	107	1428	4.15	<10	1.39	1733	13	0.01	5	870	34	15	<20	117	0.04	<10	19	<10	6	77
20	X10796	4.3	0.86	5	55	<5	2.05	2	11	121	2564	3.86	<10	1.23	1681	13	0.01	6	830	32	10	<20	134	0.03	<10	18	<10	5	49
21	X10797	2.6	1.39	<5	55	<5	1.02	2	11	105	1752	4.11	<10	1.21	763	25	0.02	5	920	34	15	<20	108	0.02	<10	32	<10	3	83
22	X10798	1.8	1.41	<5	65	<5	1.08	2	11	116	1409	4.48	<10	1.22	803	18	0.04	5	1160	38	15	<20	125	0.03	<10	60	<10	3	94
23	X10799	2.9	1.49	<5	70	<5	1.38	2	12	112	2432	4.26	<10	1.48	1090	22	0.03	6	970	46	15	<20	149	0.03	<10	57	<10	3	97
24	X10800	2.7	1.61	<5	50	<5	3.31	2	11	136	1984	4.66	<10	2.73	2743	15	0.02	7	1070	42	20	<20	146	0.05	<10	50	<10	9	87
25	X10801	2.8	1.84	<5	75	<5	0.96	2	17	76	2260	5.93	<10	1.71	929	26	0.03	5	1250	48	10	<20	128	0.04	<10	67	<10	4	101

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10802	4.1	1.40	<5	65	<5	1.12	2	13	159	3424	5.74	<10	1.31	1197	19	0.03	7	1100	46	10	<20	104	0.04	<10	53	<10	3	86
27	X10803	3.6	1.14	45	75	<5	0.78	5	18	64	3412	3.80	20	0.60	290	215	0.04	14	330	150	40	<20	43	0.05	<10	49	<10	7	165
28	X10804	1.7	1.53	<5	65	<5	1.32	1	13	96	1361	5.00	<10	1.58	1234	21	0.03	5	1180	38	15	<20	130	0.04	<10	59	<10	3	99
29	X10805	1.4	1.52	<5	100	<5	1.73	3	12	131	1277	4.24	<10	1.53	1268	23	0.03	9	1240	40	25	<20	186	0.03	<10	44	<10	4	109
30	X10806	<0.2	0.03	15	<5	<5	>10	<1	1	4	4	0.03	<10	2.00	23	<1	<0.01	<1	40	8	25	<20	6599	<0.01	<10	3	<10	<1	<1
31	X10807	2.5	1.32	<5	65	<5	1.20	1	12	103	1889	4.49	<10	1.43	1107	18	0.02	5	1160	44	10	<20	121	0.04	<10	38	<10	5	87
32	X10808	4.4	1.54	<5	60	<5	1.61	2	13	128	4317	4.40	<10	1.70	1171	17	0.02	6	990	38	15	<20	152	0.03	<10	48	<10	5	89
33	X10809	2.6	1.54	<5	50	<5	1.81	2	14	100	1862	4.48	<10	1.81	1321	24	0.02	6	1230	40	20	<20	154	0.03	<10	38	<10	5	82
34	X10810	2.3	1.47	<5	50	<5	1.60	2	14	77	1574	4.24	<10	1.62	1103	26	0.02	5	1330	40	15	<20	143	0.03	<10	42	<10	5	81
35	X10811	3.1	1.28	<5	55	<5	1.38	1	13	86	2202	3.75	<10	1.46	1098	36	0.02	5	1280	38	15	<20	129	0.03	<10	35	<10	5	81
QC DATA:																													
Repeat:																													
1	X10777	1.7	0.81	15	70	<5	3.32	1	7	70	850	2.07	<10	0.48	1577	14	0.01	2	1100	22	5	<20	135	0.03	<10	12	<10	6	41
10	X10786	4.1	0.99	30	55	<5	2.03	3	10	85	2046	3.99	<10	1.02	1738	18	0.02	5	1020	26	10	<20	79	0.03	<10	19	<10	4	74
19	X10795	3.1	1.10	<5	55	<5	1.78	2	11	105	1440	4.12	<10	1.40	1727	15	0.01	5	870	30	15	<20	109	0.03	<10	19	<10	4	77
Resplit:																													
1	X10777	1.9	0.80	10	60	<5	3.31	1	7	75	906	2.24	<10	0.50	1579	14	0.01	4	1150	24	10	<20	134	0.03	<10	13	<10	6	43
Standard:																													
PB113A		11.6	0.23	50	65	<5	1.64	30	3	6	2215	1.10	<10	0.12	1481	71	0.02	2	90	5550	25	<20	94	0.02	<10	9	<10	<1	6956

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish



ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5735S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5737

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

6-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07217
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10567	2.19	0.064
2	X10568	0.76	0.022
3	X10569	0.33	0.010
4	X10570	0.40	0.012
5	X10571	<0.03	<0.001
6	X10572	0.71	0.021
7	X10573	0.50	0.015
8	X10574	1.28	0.037
9	X10575	1.25	0.036
10	X10576	0.67	0.020
11	X10577	0.29	0.008
12	X10578	0.92	0.027
13	X10579	1.04	0.030
14	X10580	0.81	0.024
15	X10581	1.54	0.045
16	X10582	1.16	0.034
17	X10583	0.68	0.020
18	X10584	0.74	0.022
19	X10585	0.68	0.020
20	X10586	0.39	0.011
21	X10587	0.54	0.016
22	X10588	0.55	0.016
23	X10589	0.85	0.025
24	X10590	1.07	0.031
25	X10591	0.96	0.028
26	X10592	1.04	0.030
27	X10593	0.29	0.008
28	X10594	1.06	0.031
29	X10595	0.67	0.020

ECO TECH LABORATORY LTD.
Ivuta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5737 6-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X10596	1.06	0.031
31	X10597	0.78	0.023
32	X10598	1.13	0.033
33	X10599	1.23	0.036
34	X10600	0.71	0.021
35	X10601	1.32	0.038

QC DATA:

Repeat:

1	X10567	2.27	0.066
8	X10574	1.17	0.034
10	X10576	0.65	0.019
15	X10581	1.53	0.045
16	X10582	1.22	0.036
19	X10585	0.68	0.020
24	X10590	0.92	0.027
26	X10592	1.00	0.029

Resplits:

1	X10567	2.28	0.066
	X10576		
Standarc	X10585		
SN26		8.59	0.251

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

5 Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5737

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07217
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10567	2.6	0.20	<5	50	<5	2.23	1	10	121	3128	4.35	<10	0.16	583	10	0.01	5	620	22	<5	<20	148	0.02	<10	8	<10	1	23
2	X10568	2.7	0.20	<5	40	<5	2.28	2	10	129	3820	4.34	<10	<0.01	448	11	0.01	4	410	30	10	<20	179	0.02	<10	6	<10	<1	53
3	X10569	5.1	0.22	20	50	<5	0.24	3	12	190	4726	5.01	<10	<0.01	72	12	0.01	8	340	36	50	<20	45	0.02	<10	5	<10	<1	34
4	X10570	4.9	0.23	<5	40	<5	0.25	3	16	182	6300	5.82	<10	<0.01	96	13	0.01	9	220	36	30	<20	34	<0.01	<10	7	<10	<1	18
5	X10571	<0.2	0.02	15	<5	10	>10	<1	1	2	7	0.02	<10	1.94	17	<1	<0.01	<1	60	8	25	<20	6709	<0.01	<10	3	<10	<1	<1
6	X10572	3.3	0.23	<5	35	<5	0.28	3	10	154	2428	4.83	<10	<0.01	59	14	<0.01	6	540	58	<5	<20	35	0.02	<10	6	<10	<1	102
7	X10573	2.2	0.24	<5	45	<5	1.32	2	8	152	2741	4.43	<10	<0.01	244	11	0.01	6	570	38	<5	<20	115	0.02	<10	8	<10	<1	37
8	X10574	2.7	0.19	<5	45	<5	1.88	2	11	159	3617	4.66	<10	0.25	574	10	<0.01	7	360	18	<5	<20	113	0.02	<10	8	<10	<1	11
9	X10575	2.4	0.55	<5	45	<5	0.88	1	8	125	2811	3.62	<10	0.67	572	14	0.01	6	770	18	10	<20	29	0.02	<10	11	<10	2	36
10	X10576	2.6	0.22	<5	35	<5	1.26	4	15	141	3956	4.99	<10	0.02	313	13	0.01	6	520	34	<5	<20	106	0.02	<10	7	<10	<1	184
11	X10577	3.2	1.14	30	60	<5	0.99	3	22	55	2655	3.55	20	0.67	198	193	0.03	10	460	56	15	<20	61	0.06	<10	47	<10	7	264
12	X10578	1.8	0.56	<5	40	<5	1.76	<1	8	122	2530	3.32	<10	0.41	454	17	0.01	4	700	24	<5	<20	148	0.02	<10	14	<10	3	44
13	X10579	1.6	0.41	<5	40	<5	2.85	1	9	132	2549	3.26	<10	0.24	682	9	0.01	4	700	32	<5	<20	193	0.02	<10	13	<10	2	31
14	X10580	1.2	0.40	<5	40	<5	2.90	1	7	113	1670	3.04	<10	0.18	524	14	0.01	5	800	24	<5	<20	220	0.02	<10	13	<10	2	25
15	X10581	1.8	0.50	<5	45	<5	2.05	6	8	143	2656	3.64	<10	0.34	494	14	0.01	6	610	34	<5	<20	169	0.02	<10	15	<10	1	285
16	X10582	1.8	0.45	<5	40	<5	1.55	1	8	125	2452	3.94	<10	0.37	508	12	0.01	5	770	26	<5	<20	115	0.02	<10	11	<10	2	38
17	X10583	2.7	0.25	<5	45	<5	0.70	2	12	152	3163	4.86	<10	0.03	300	13	0.01	6	670	60	<5	<20	65	0.02	<10	6	<10	<1	75
18	X10584	2.8	0.21	<5	50	<5	0.57	2	15	142	2795	4.76	<10	0.02	247	15	0.01	6	540	54	<5	<20	42	0.02	<10	5	<10	<1	42
19	X10585	8.8	0.24	100	45	<5	0.14	4	10	190	3232	4.48	<10	<0.01	45	11	<0.01	7	350	64	30	<20	44	0.02	<10	6	<10	<1	136
20	X10586	2.1	0.21	<5	45	<5	1.74	2	10	138	2278	4.45	<10	0.02	391	11	0.01	5	620	38	<5	<20	160	0.03	<10	6	<10	1	70
21	X10587	1.6	0.54	<5	45	<5	1.76	<1	6	125	2039	3.43	<10	0.39	592	11	0.01	6	870	34	<5	<20	131	0.02	<10	12	<10	2	39
22	X10588	2.6	0.61	<5	45	<5	1.68	2	14	148	2380	4.27	<10	0.39	421	12	0.01	5	770	32	5	<20	104	0.02	<10	13	<10	2	42
23	X10589	1.8	0.49	<5	45	<5	2.78	2	11	125	2428	3.85	<10	0.30	555	11	0.01	4	680	28	<5	<20	178	0.02	<10	14	<10	1	45
24	X10590	2.3	0.53	<5	50	<5	1.76	2	9	124	2616	3.75	<10	0.39	729	13	0.01	8	740	24	10	<20	100	0.02	<10	13	<10	3	75
25	X10591	1.8	0.41	<5	40	<5	2.20	2	8	130	2401	3.47	<10	0.22	740	12	0.01	4	680	32	<5	<20	125	0.02	<10	8	<10	2	39

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10592	2.9	0.58	<5	40	<5	2.16	5	9	143	3543	3.24	<10	0.41	665	14	0.01	5	660	104	<5	<20	142	0.02	<10	11	<10	<1	306
27	X10593	2.6	0.22	<5	40	<5	0.95	2	27	164	2750	5.20	<10	0.06	378	15	0.01	7	410	74	<5	<20	95	0.03	<10	6	<10	<1	55
28	X10594	2.3	0.64	<5	45	<5	1.91	2	7	157	2916	3.83	<10	0.46	649	16	0.01	6	530	34	<5	<20	118	0.02	<10	15	<10	<1	51
29	X10595	2.7	0.40	<5	55	<5	0.72	2	12	134	2837	4.62	<10	0.17	421	10	0.01	6	670	50	<5	<20	59	0.03	<10	10	<10	<1	42
30	X10596	2.6	0.84	<5	45	<5	0.40	1	10	134	2909	3.84	<10	0.68	353	12	0.01	4	770	42	5	<20	27	0.02	<10	15	<10	1	53
31	X10597	1.7	0.87	<5	50	<5	1.05	<1	9	149	2011	3.46	<10	0.65	406	12	0.01	5	790	24	<5	<20	57	0.02	<10	17	<10	<1	43
32	X10598	2.5	0.82	<5	55	<5	0.70	1	9	154	3009	4.20	<10	0.62	393	12	0.01	6	660	28	<5	<20	59	0.03	<10	18	<10	2	45
33	X10599	2.6	0.44	<5	45	<5	1.12	1	12	158	3981	4.41	<10	0.27	383	12	0.01	6	430	30	<5	<20	85	0.03	<10	11	<10	2	24
34	X10600	4.0	0.22	<5	50	<5	0.37	2	11	155	5281	6.02	<10	<0.01	136	8	0.01	6	330	44	<5	<20	57	0.03	<10	7	<10	<1	35
35	X10601	4.2	0.33	<5	55	<5	1.50	1	11	152	6310	5.03	<10	0.12	431	10	0.01	5	270	20	<5	<20	102	0.02	<10	8	<10	<1	14
QC DATA:																													
Repeat:																													
1	X10567	2.4	0.19	<5	40	<5	2.12	1	9	116	3090	4.32	<10	0.16	577	10	0.01	4	600	18	<5	<20	135	0.02	<10	9	<10	<1	23
10	X10576	2.7	0.20	<5	40	<5	1.24	4	16	135	3895	5.00	<10	0.01	311	14	0.01	6	550	38	<5	<20	112	0.03	<10	7	<10	<1	191
19	X10585	9.0	0.24	105	40	<5	0.14	4	10	187	3315	4.61	<10	<0.01	47	11	<0.01	7	330	64	30	<20	40	0.02	<10	5	<10	<1	137
Resplit:																													
1	X10567	2.6	0.21	<5	55	<5	2.31	2	11	127	3104	4.66	<10	0.15	604	10	0.01	6	640	18	<5	<20	139	0.02	<10	9	<10	<1	21
Standard:																													
PB113A		11.2	0.26	45	65	<5	1.66	40	3	7	2204	1.10	<10	0.12	1485	60	0.02	2	110	5560	25	<20	80	0.02	<10	9	<10	1	6970

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5735S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5738

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

6-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07203
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X14071	0.84	0.024
2	X14072	0.79	0.023
3	X14073	0.77	0.022
4	X14074	0.77	0.022
5	X14075	0.80	0.023
6	X14076	1.69	0.049
7	X14077	1.32	0.038
8	X14078	1.43	0.042
9	X14079	0.89	0.026
10	X14080	1.08	0.031
11	X14081	1.33	0.039
12	X14082	0.67	0.020
13	X14083	1.79	0.052
14	X14084	0.89	0.026
15	X14085	0.53	0.015
16	X14086	0.93	0.027
17	X14087	0.53	0.015
18	X14088	1.48	0.043
19	X14089	0.57	0.017
20	X14090	0.64	0.019
21	X14091	1.52	0.044
22	X14092	1.08	0.031
23	X14093	1.12	0.033
24	X14094	0.90	0.026
25	X14095	1.74	0.051
26	X14096	1.01	0.029
27	X14097	0.56	0.016
28	X14098	1.08	0.031
29	X14099	0.49	0.014

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5738 6-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X14100	1.23	0.036
31	X14101	1.28	0.037
32	X14102	0.86	0.025
33	X14103	0.90	0.026
34	X14104	1.04	0.030
35	X14105	<0.03	<0.001
QC DATA:			
Repeat:			
1	X14071	0.88	0.026
6	X14076	1.73	0.050
7	X14077	1.32	0.038
8	X14078	1.39	0.041
10	X14080	1.12	0.033
13	X14083	1.68	0.049
19	X14089	0.63	0.018
25	X14095	1.76	0.051
Resplits:			
1	X14071	0.88	0.026
Standard:			
SN26		8.60	0.251

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

5 Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5738

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07203
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X14071	1.8	0.74	10	60	<5	0.27	<1	16	100	1729	5.75	<10	0.37	423	79	0.02	5	950	68	<5	<20	48	0.04	<10	16	<10	2	145
2	X14072	1.5	0.82	<5	40	<5	0.24	2	17	106	1483	6.03	<10	0.43	462	56	0.02	6	890	90	<5	<20	29	0.04	<10	17	<10	<1	193
3	X14073	1.9	0.70	10	40	<5	0.23	<1	15	118	1588	5.50	<10	0.36	409	50	0.02	6	840	56	<5	<20	28	0.03	<10	13	<10	<1	177
4	X14074	1.6	0.53	5	45	<5	0.37	3	15	104	1196	5.19	<10	0.22	334	135	0.02	7	1520	128	<5	<20	29	0.03	<10	15	<10	<1	259
5	X14075	1.3	0.50	10	50	<5	0.31	2	17	128	1591	5.06	<10	0.19	280	54	0.02	8	1220	86	<5	<20	39	0.03	<10	15	<10	2	300
6	X14076	1.7	0.57	5	45	<5	0.31	<1	20	99	2383	6.22	<10	0.26	292	67	0.02	9	1130	46	<5	<20	40	0.04	<10	12	<10	<1	147
7	X14077	1.1	0.73	<5	40	<5	0.25	<1	16	150	1868	5.35	<10	0.35	348	83	0.02	9	930	60	<5	<20	31	0.03	<10	16	<10	<1	186
8	X14078	1.7	0.48	15	45	<5	0.26	2	19	129	2298	6.36	<10	0.18	231	71	0.01	9	930	46	<5	<20	36	0.03	<10	11	<10	<1	149
9	X14079	1.4	0.33	25	35	<5	0.22	1	12	162	1449	5.30	<10	0.07	112	62	0.01	9	880	30	<5	<20	28	0.02	<10	10	<10	<1	125
10	X14080	1.3	0.35	25	50	<5	0.21	<1	12	161	899	4.39	<10	0.12	158	68	0.02	9	840	28	<5	<20	38	0.03	<10	10	<10	2	103
11	X14081	1.9	0.51	<5	45	<5	0.33	2	20	148	1943	6.26	<10	0.18	191	61	0.02	14	1250	38	<5	<20	42	0.03	<10	13	<10	<1	146
12	X14082	2.1	0.37	<5	35	<5	0.27	3	17	100	1823	5.58	<10	0.13	160	50	0.01	11	1010	118	<5	<20	25	0.03	<10	9	<10	<1	212
13	X14083	1.5	0.37	10	40	<5	0.24	3	12	183	1190	5.11	<10	0.09	172	79	0.02	16	830	106	<5	<20	27	0.03	<10	7	<10	<1	285
14	X14084	2.0	0.42	5	35	<5	0.22	3	13	137	2102	5.08	<10	0.16	186	47	0.01	16	770	76	<5	<20	29	0.03	<10	10	<10	<1	299
15	X14085	1.6	0.39	<5	60	<5	0.23	2	15	184	1964	5.21	<10	0.07	127	93	0.02	16	840	200	<5	<20	46	0.04	<10	6	<10	1	250
16	X14086	2.0	0.59	<5	40	<5	0.19	3	18	114	2336	6.18	<10	0.32	296	71	0.02	19	710	126	<5	<20	21	0.03	<10	10	<10	<1	330
17	X14087	1.8	0.41	<5	35	<5	0.16	2	15	169	3084	5.28	<10	0.15	164	61	0.02	15	500	124	<5	<20	20	0.03	<10	6	<10	<1	167
18	X14088	2.1	0.49	<5	45	<5	0.29	1	20	120	2296	6.26	<10	0.21	240	84	0.02	21	1170	44	<5	<20	37	0.03	<10	8	<10	<1	134
19	X14089	5.5	0.42	10	35	<5	0.11	2	13	196	2234	4.39	<10	0.16	173	62	0.02	14	330	120	<5	<20	30	0.02	<10	7	<10	<1	269
20	X14090	1.7	0.24	<5	30	<5	0.14	2	14	143	2034	4.69	<10	0.02	67	81	0.02	12	450	62	<5	<20	31	0.02	<10	5	<10	<1	135
21	X14091	1.8	0.33	<5	35	<5	0.21	2	18	155	2311	6.57	<10	0.04	119	123	0.02	18	730	52	<5	<20	32	0.03	<10	8	<10	<1	168
22	X14092	1.3	0.25	10	35	<5	0.12	2	15	128	2458	5.10	<10	0.03	66	85	0.02	15	310	42	<5	<20	34	0.02	<10	6	<10	<1	121
23	X14093	1.2	0.32	15	30	<5	0.12	2	14	209	2258	4.76	<10	0.03	80	87	0.02	15	360	42	<5	<20	25	0.02	<10	7	<10	<1	135
24	X14094	1.6	0.23	20	45	<5	0.11	1	15	137	2307	4.61	<10	<0.01	50	49	0.02	13	300	52	<5	<20	44	0.02	<10	4	<10	<1	116
25	X14095	2.1	0.28	<5	30	<5	0.12	7	14	181	2777	4.53	<10	0.04	87	70	0.02	15	330	162	<5	<20	31	0.02	<10	6	<10	<1	962

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X14096	1.9	0.28	10	45	<5	0.23	8	16	142	2161	4.91	<10	0.05	107	102	0.02	15	880	448	<5	<20	35	0.03	<10	6	<10	<1	1295
27	X14097	1.0	0.44	10	35	<5	0.21	<1	11	299	1247	4.38	<10	0.19	308	72	0.02	17	570	90	<5	<20	29	0.02	<10	8	<10	<1	115
28	X14098	1.8	0.38	15	35	<5	0.18	1	16	167	2083	4.67	<10	0.16	201	75	0.02	12	600	110	<5	<20	26	0.02	<10	8	<10	<1	139
29	X14099	1.0	0.61	15	30	<5	0.11	3	8	231	848	3.07	<10	0.45	368	36	0.01	9	280	108	<5	<20	14	0.02	<10	9	<10	<1	576
30	X14100	1.7	0.44	15	35	<5	0.21	<1	14	168	1951	4.34	<10	0.21	199	89	0.02	11	780	72	<5	<20	28	0.02	<10	8	<10	2	108
31	X14101	1.8	0.30	10	35	<5	0.14	<1	16	169	2329	5.08	<10	0.05	92	74	0.02	16	420	38	<5	<20	19	0.02	<10	7	<10	<1	34
32	X14102	1.3	0.22	15	30	<5	0.09	<1	13	164	1991	3.85	<10	0.01	68	134	0.02	10	270	28	<5	<20	2	0.02	<10	4	<10	<1	22
33	X14103	2.8	0.45	90	50	<5	0.34	1	17	207	1853	6.65	<10	0.16	150	434	0.02	20	1380	102	5	<20	34	0.03	<10	9	<10	1	92
34	X14104	3.6	1.09	65	50	<5	0.76	3	47	56	3419	3.84	20	0.57	283	212	0.03	13	330	140	35	<20	27	0.04	<10	46	<10	4	161
35	X14105	<0.2	0.05	50	<5	10	>10	<1	2	4	9	0.04	<10	2.13	23	1	<0.01	<1	40	10	30	<20	6457	<0.01	<10	5	<10	<1	<1
QC DATA:																													
Repeat:																													
1	X14071	1.7	0.76	<5	55	<5	0.27	<1	15	99	1764	5.78	<10	0.38	423	80	0.02	6	930	60	<5	<20	41	0.03	<10	16	<10	1	143
10	X14080	1.4	0.35	15	55	<5	0.21	<1	12	161	876	4.38	<10	0.12	171	76	0.01	10	820	28	<5	<20	40	0.03	<10	11	<10	2	102
19	X14089	5.4	0.44	5	30	<5	0.11	3	13	199	2297	4.44	<10	0.18	178	67	0.02	14	330	118	<5	<20	28	0.02	<10	8	<10	<1	266
Resplit:																													
1	X14071	1.6	0.74	<5	55	<5	0.29	<1	15	108	1686	5.56	<10	0.38	407	76	0.02	5	950	66	<5	<20	40	0.03	<10	16	<10	1	140
Standard:																													
PB113A		11.4	0.26	45	65	<5	1.77	30	3	6	2250	1.09	<10	0.12	1483	68	0.02	2	60	5584	25	<20	88	0.02	<10	9	<10	<1	6971

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5735S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5739

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

6-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07218
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	X10602	0.39	0.011		
2	X10603	0.10	0.003		
3	X10604	0.98	0.029		
4	X10605	0.84	0.024		
5	X10606	0.53	0.015		
6	X10607	1.26	0.037		
7	X10608	<0.03	<0.001		
8	X10609	0.71	0.021	56.2	1.64
9	X10610	0.41	0.012	64.1	1.87
10	X10611	0.37	0.011		
11	X10612	0.44	0.013	58.3	1.70
12	X10613	0.45	0.013		
13	X10614	0.50	0.015		
14	X10615	0.59	0.017		
15	X10616	0.70	0.020		
16	X10617	0.81	0.024		
17	X10618	0.80	0.023		
18	X10619	0.76	0.022		
19	X10620	0.72	0.021		
20	X10621	1.01	0.029		
21	X10622	1.07	0.031		
22	X10623	0.37	0.011		
23	X10624	0.53	0.015		
24	X10625	<0.03	<0.001		
25	X10626	1.02	0.030		
26	X10627	1.38	0.040		
27	X10628	1.13	0.033		
28	X10629	1.40	0.041		
29	X10630	0.36	0.010		

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5739 06-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
30	X10631	0.24	0.007		
31	X10632	0.99	0.029		
32	X10633	0.47	0.014		
33	X10634	0.88	0.026		
34	X10635	0.93	0.027		
35	X10636	1.83	0.053		
QC DATA:					
Repeat:					
1	X10602	0.30	0.009		
8	X10609			60.0	1.75
10	X10611	0.37	0.011		
19	X10620	0.70	0.020		
Resplits:					
1	X10602	0.32	0.009		
Standard:					
SN26		8.59	0.251		
PB113				22.4	0.65

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

4-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5739

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07218
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10602	3.2	0.21	25	35	<5	0.97	3	9	144	3247	5.55	<10	0.02	315	9	0.02	<1	730	42	20	<20	78	<0.01	<10	6	<10	1	35
2	X10603	2.4	0.20	65	40	<5	0.35	3	18	130	957	7.83	<10	0.01	113	122	0.02	<1	550	30	30	<20	45	<0.01	<10	2	<10	<1	43
3	X10604	7.2	0.21	20	35	<5	0.37	4	10	143	4052	6.12	<10	0.02	164	8	0.02	<1	770	72	5	<20	19	<0.01	<10	4	<10	1	100
4	X10605	5.8	0.21	25	40	<5	0.35	3	18	143	3642	6.61	<10	0.03	197	12	0.02	2	740	48	10	<20	26	<0.01	<10	6	<10	<1	48
5	X10606	10.1	0.20	25	30	<5	0.29	3	8	170	3120	4.86	<10	0.01	119	8	0.01	3	640	48	10	<20	18	<0.01	<10	4	<10	1	19
6	X10607	13.3	0.58	55	30	<5	0.70	2	15	191	1368	4.00	<10	0.51	691	7	0.01	28	520	22	10	<20	28	<0.01	<10	7	<10	1	53
7	X10608	1.0	3.71	65	60	<5	0.27	2	25	99	302	6.38	<10	3.95	1118	<1	0.02	101	1240	<2	<5	<20	15	<0.01	<10	54	<10	3	385
8	X10609	>30	0.21	90	40	<5	0.91	7	13	180	4375	6.44	<10	0.17	1565	13	0.02	2	660	116	165	<20	36	<0.01	<10	5	<10	2	179
9	X10610	>30	0.25	65	35	<5	0.94	7	11	149	3032	6.35	<10	0.17	1785	7	0.01	2	810	296	70	<20	35	<0.01	<10	5	<10	2	152
10	X10611	28.3	0.24	55	35	<5	0.86	6	5	114	1273	5.20	<10	0.15	1048	12	0.01	1	1100	76	35	<20	34	<0.01	<10	4	<10	3	135
11	X10612	>30	0.24	160	40	<5	0.47	11	7	188	2149	4.86	<10	0.02	258	9	0.01	3	810	328	165	<20	37	<0.01	<10	5	<10	2	414
12	X10613	23.2	0.21	140	35	<5	0.27	6	9	148	2448	5.26	<10	0.02	134	8	0.01	2	810	46	80	<20	22	<0.01	<10	4	<10	2	150
13	X10614	19.4	0.20	30	55	5	0.84	8	13	174	4860	6.39	<10	0.17	644	10	0.02	2	730	70	30	<20	40	<0.01	<10	3	<10	1	183
14	X10615	8.9	0.40	5	35	5	0.95	3	10	156	4911	5.44	<10	0.46	873	10	0.01	1	660	78	<5	<20	50	<0.01	<10	9	<10	2	60
15	X10616	2.6	0.93	10	40	<5	0.65	1	5	131	2387	3.92	<10	0.66	488	12	0.01	2	990	12	<5	<20	42	<0.01	<10	15	<10	3	56
16	X10617	2.3	0.98	15	45	<5	0.77	2	5	137	3131	4.60	<10	0.76	655	11	0.01	2	850	26	<5	<20	54	<0.01	<10	12	<10	3	63
17	X10618	2.7	0.84	10	45	<5	0.67	2	8	148	3909	4.75	<10	0.65	552	11	0.02	2	790	32	<5	<20	46	<0.01	<10	11	<10	2	58
18	X10619	3.5	0.66	10	40	<5	0.64	2	14	110	3466	4.93	<10	0.55	531	10	0.02	1	970	26	<5	<20	36	<0.01	<10	11	<10	2	38
19	X10620	3.4	0.66	15	35	<5	0.43	2	7	147	1928	3.95	<10	0.62	447	10	0.02	3	820	44	<5	<20	22	<0.01	<10	13	<10	2	44
20	X10621	2.4	0.90	10	40	<5	0.85	2	9	104	2134	4.68	<10	0.84	724	9	0.02	<1	980	18	<5	<20	51	<0.01	<10	14	<10	3	45
21	X10622	3.4	0.79	10	40	<5	0.79	2	8	160	3136	5.42	<10	0.65	654	10	0.02	2	710	32	<5	<20	47	<0.01	<10	10	<10	2	72
22	X10623	3.0	0.19	<5	40	<5	1.28	7	12	135	3109	5.89	<10	0.23	857	10	0.02	<1	680	76	<5	<20	68	<0.01	<10	6	<10	2	255
23	X10624	3.0	0.24	5	35	<5	0.72	14	10	163	3089	5.93	<10	0.12	412	8	0.02	2	810	262	5	<20	46	<0.01	<10	8	<10	2	782
24	X10625	<0.2	0.01	<5	<5	<5	>10	<1	<1	2	4	0.03	<10	1.36	28	<1	<0.01	1	30	<2	<5	<20	6722	<0.01	<10	<1	<10	<1	1
25	X10626	2.7	0.57	10	45	<5	1.36	3	11	152	2525	4.91	<10	0.52	873	8	0.01	2	750	50	<5	<20	63	<0.01	<10	6	<10	2	54

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10627	2.6	0.80	15	45	<5	0.94	3	9	126	2733	5.44	<10	0.65	856	10	0.01	1	830	35	<5	<20	44	<0.01	<10	11	<10	2	77
27	X10628	2.5	1.21	15	55	<5	1.26	4	8	132	3071	5.92	<10	0.98	1089	8	0.01	<1	910	28	<5	<20	62	<0.01	<10	13	<10	3	115
28	X10629	4.2	0.20	5	50	<5	1.38	5	12	141	4858	7.05	<10	0.31	923	30	0.01	<1	780	48	<5	<20	61	<0.01	<10	5	<10	2	46
29	X10630	5.7	0.18	20	45	<5	1.47	6	12	139	5223	5.68	<10	0.36	1207	6	0.01	<1	660	96	15	<20	59	<0.01	<10	2	<10	2	114
30	X10631	4.1	0.17	25	50	<5	1.82	6	12	185	3081	6.03	<10	0.56	1584	22	0.01	2	460	110	20	<20	61	<0.01	<10	2	<10	3	142
31	X10632	3.6	1.01	70	65	10	0.78	5	16	59	3301	4.35	20	0.48	320	219	0.03	17	510	108	35	<20	47	0.03	<10	36	<10	8	165
32	X10633	2.8	0.22	5	40	<5	0.86	4	11	147	2776	5.01	<10	0.21	650	9	0.01	2	1010	46	<5	<20	33	<0.01	<10	3	<10	3	99
33	X10634	2.3	0.21	10	45	<5	1.24	7	11	151	2523	6.91	<10	0.35	1132	8	0.01	1	1030	86	<5	<20	43	<0.01	<10	4	<10	2	143
34	X10635	2.7	0.25	5	40	<5	1.09	4	16	173	3450	5.80	<10	0.21	775	9	0.01	2	860	58	<5	<20	36	<0.01	<10	5	<10	2	34
35	X10636	3.0	0.55	10	50	<5	1.65	4	11	160	3706	5.66	<10	0.56	1038	8	<0.01	3	770	44	<5	<20	49	<0.01	<10	7	<10	2	72
QC DATA:																													
Repeat:																													
1	X10602	3.2	0.22	25	35	<5	1.00	3	9	152	3291	5.71	<10	0.02	329	9	0.02	1	770	42	20	<20	86	<0.01	<10	6	<10	1	35
10	X10611	24.0	0.26	60	30	<5	0.89	7	5	120	1337	5.29	<10	0.16	1145	14	0.01	1	1170	82	40	<20	35	<0.01	<10	6	<10	3	143
19	X10620	3.4	0.69	15	40	<5	0.49	3	8	156	1946	4.42	<10	0.60	460	11	0.01	3	840	44	<5	<20	24	<0.01	<10	12	<10	2	48
Resplit:																													
1	X10602	3.2	0.21	25	40	<5	1.02	5	14	151	3329	7.33	<10	0.02	322	10	0.01	<1	770	46	15	<20	80	<0.01	<10	4	<10	1	37
Standard:																													
PB113A		11.8	0.26	50	60	<5	1.67	37	2	<1	2295	1.25	<10	0.10	1573	69	0.01	1	90	5610	10	<20	87	0.01	<10	5	<10	1	7032

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/n5739
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5740

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

6-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07212
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05973	0.32	0.009
2	X05974	0.57	0.017
3	X05975	0.07	0.002
4	X05976	0.53	0.015
5	X05977	0.39	0.011
6	X05978	0.73	0.021
7	X05979	1.35	0.039
8	X05980	0.96	0.028
9	X05981	0.78	0.023
10	X05982	0.46	0.013
11	X05983	0.56	0.016
12	X05984	0.50	0.015
13	X05985	0.51	0.015
14	X05986	0.47	0.014
15	X05987	0.55	0.016
16	X05988	0.65	0.019
17	X05989	0.33	0.010
18	X05990	0.31	0.009
19	X05991	0.60	0.017
20	X05992	0.21	0.006
21	X05993	0.35	0.010
22	X05994	0.43	0.013
23	X05995	0.29	0.008
24	X05996	0.28	0.008
25	X05997	0.28	0.008
26	X05998	<0.03	<0.001
27	X05999	0.32	0.009
28	X06000	0.48	0.014
29	X06001	0.50	0.015

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5740 6-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X06002	0.23	0.007
31	X06003	0.34	0.010
32	X06004	0.40	0.012
33	X06005	0.32	0.009
34	X06006	0.41	0.012
35	X06007	0.43	0.013
QC DATA:			
Repeat:			
1	X05973	0.30	0.009
10	X05982	0.50	0.015
19	X05991	0.55	0.016
Resplits:			
1	X05973	0.34	0.010
Standard:			
SN26		8.57	0.250

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

4-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007- 5740

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07212
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05973	1.8	1.13	50	70	<5	5.11	2	11	56	1134	3.66	<10	0.85	1797	17	0.01	4	1020	20	<5	<20	179	<0.01	<10	23	<10	6	77
2	X05974	3.2	0.64	30	55	<5	4.64	2	14	103	3079	3.83	<10	0.44	1566	14	0.01	4	804	16	<5	<20	184	<0.01	<10	18	<10	7	40
3	X05975	0.5	0.92	95	160	15	0.35	8	61	225	447	>10	10	0.20	515	122	0.05	481	158	118	5	<20	13	<0.01	<10	19	<10	6	402
4	X05976	2.0	1.13	30	65	<5	3.94	3	12	89	1746	5.52	<10	0.79	1460	10	0.01	4	828	14	<5	<20	192	0.01	<10	62	<10	5	62
5	X05977	1.8	1.19	25	90	<5	3.21	3	11	78	1614	4.33	<10	0.88	1305	9	0.02	5	1014	8	<5	<20	157	0.01	<10	46	<10	7	65
6	X05978	3.0	1.24	30	100	<5	3.28	2	13	82	3142	4.11	<10	0.99	1243	19	0.02	5	1002	8	<5	<20	196	0.02	<10	49	<10	8	66
7	X05979	4.0	1.32	15	120	<5	2.07	3	15	85	3808	4.55	<10	1.07	921	12	0.02	5	978	10	<5	<20	154	0.02	<10	79	<10	7	76
8	X05980	3.2	1.42	15	110	<5	1.97	3	16	76	4130	5.06	<10	1.18	919	14	0.02	5	1032	10	<5	<20	141	0.02	<10	89	<10	7	85
9	X05981	2.6	1.29	15	130	<5	2.51	3	14	79	2917	4.76	<10	1.10	982	21	0.03	5	1014	12	<5	<20	172	0.03	<10	95	<10	6	75
10	X05982	2.1	1.27	20	145	<5	2.79	4	14	83	2158	5.27	<10	0.98	1253	24	0.02	5	1044	8	<5	<20	200	0.01	<10	76	<10	7	102
11	X05983	1.8	1.19	15	240	<5	2.59	3	14	65	2178	4.93	<10	0.93	1031	25	0.04	5	1092	6	<5	<20	215	0.02	<10	111	<10	6	76
12	X05984	2.0	1.14	25	110	<5	3.42	3	13	59	1984	4.89	<10	0.85	1362	24	0.01	4	978	16	<5	<20	189	0.01	<10	57	<10	7	75
13	X05985	2.0	1.18	20	100	<5	2.62	2	15	97	2003	4.17	<10	0.90	1130	30	0.02	6	834	12	<5	<20	143	0.01	<10	46	<10	7	64
14	X05986	2.1	1.06	15	150	<5	3.14	2	13	76	1782	4.01	<10	0.78	1208	28	0.02	5	984	8	<5	<20	177	0.01	<10	51	<10	7	69
15	X05987	2.4	0.94	15	120	<5	4.51	2	16	70	2063	3.91	<10	0.58	1666	22	0.02	6	1038	8	<5	<20	204	0.01	<10	32	<10	8	56
16	X05988	3.0	1.01	15	115	<5	4.38	3	16	75	2706	4.78	<10	0.64	1869	21	0.02	5	1050	4	<5	<20	203	0.01	<10	45	<10	8	76
17	X05989	2.1	1.18	15	125	<5	4.43	3	17	73	1825	4.44	<10	0.87	1669	28	0.02	6	1068	6	<5	<20	258	0.02	<10	55	<10	8	76
18	X05990	1.7	1.13	15	120	<5	4.33	2	15	57	1527	3.75	<10	0.90	1577	28	0.02	5	1026	6	<5	<20	222	0.01	<10	43	<10	7	71
19	X05991	2.8	0.94	20	110	<5	6.17	4	18	109	2384	5.20	<10	0.62	2587	18	0.02	6	906	16	<5	<20	232	0.01	<10	92	<10	9	94
20	X05992	1.4	0.92	15	205	<5	4.55	2	12	64	1089	3.65	<10	0.60	1629	30	0.02	4	954	8	<5	<20	237	0.01	<10	37	<10	7	77
21	X05993	2.6	1.18	25	85	<5	3.98	2	16	63	1508	4.05	<10	0.79	1551	49	0.02	6	1086	14	<5	<20	164	0.01	<10	33	<10	7	89
22	X05994	2.5	1.27	20	115	<5	3.70	3	16	67	2117	4.58	<10	0.95	1473	52	0.02	5	1032	6	<5	<20	194	0.02	<10	45	<10	8	94
23	X05995	1.4	1.29	15	175	<5	3.37	3	13	68	1202	5.37	<10	1.02	1446	44	0.03	5	1092	10	<5	<20	209	0.02	<10	82	<10	7	87
24	X05996	1.5	0.99	15	345	<5	3.61	4	14	61	1267	5.74	<10	0.77	1405	85	0.03	4	1038	10	<5	<20	257	0.03	<10	102	<10	7	94
25	X05997	1.4	1.21	15	235	<5	3.14	3	15	77	1535	5.21	<10	0.98	1380	47	0.03	5	1086	8	<5	<20	235	0.03	<10	98	<10	8	103

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05998	<0.2	0.03	<5	<5	<5	>10	<1	<1	1	4	0.03	<10	1.73	38	<1	<0.01	1	36	2	<5	<20	6732	<0.01	<10	<1	<10	<1	2
27	X05999	1.8	1.26	15	145	<5	3.29	4	17	69	1704	5.55	<10	1.04	1452	32	0.03	5	1080	8	<5	<20	221	0.02	<10	110	<10	8	119
28	X06000	2.4	1.24	20	115	<5	3.27	4	17	119	2617	5.89	<10	1.01	1342	61	0.02	6	876	12	<5	<20	193	0.02	<10	106	<10	7	103
29	X06001	2.3	1.27	20	120	<5	3.79	3	16	78	2398	4.58	<10	1.03	1483	48	0.02	5	936	8	<5	<20	177	0.02	<10	60	<10	9	102
30	X06002	1.5	1.05	15	170	<5	2.98	4	14	110	1208	5.22	<10	0.84	1176	24	0.03	5	912	12	<5	<20	155	0.02	<10	108	<10	6	109
31	X06003	1.9	1.13	15	125	<5	3.40	3	16	63	1765	4.95	<10	0.91	1339	65	0.03	5	1110	12	<5	<20	203	0.02	<10	89	<10	8	115
32	X06004	2.0	1.15	15	135	<5	3.40	4	18	78	1931	5.26	<10	0.92	1300	74	0.03	6	1092	14	<5	<20	192	0.02	<10	88	<10	8	108
33	X06005	1.7	1.17	15	180	<5	3.65	4	15	64	1630	4.94	<10	0.92	1387	80	0.03	5	1110	8	<5	<20	224	0.02	<10	82	<10	8	111
34	X06006	1.8	1.08	15	170	<5	3.39	3	15	104	1724	4.97	<10	0.81	1253	50	0.03	5	942	8	<5	<20	195	0.02	<10	82	<10	7	88
35	X06007	2.3	1.16	15	115	<5	3.84	2	13	90	2112	3.93	<10	0.90	1503	62	0.02	5	990	8	<5	<20	177	0.02	<10	48	<10	8	79
QC DATA:																													
Repeat:																													
1	X05973	1.7	1.11	50	75	<5	4.75	2	11	55	1112	3.70	<10	0.84	1767	18	0.01	4	1008	18	<5	<20	181	<0.01	<10	23	<10	6	69
10	X05982	1.9	1.20	20	150	<5	2.95	4	13	79	2071	5.10	<10	0.95	1191	22	0.02	5	984	8	<5	<20	197	0.01	<10	75	<10	7	98
19	X05991	2.8	0.94	25	105	<5	6.36	4	18	112	2420	5.24	<10	0.60	2685	19	0.02	6	918	16	<5	<20	238	0.01	<10	92	<10	9	98
Resplit:																													
1	X05973	1.8	1.15	55	65	<5	5.30	2	12	60	1193	3.97	<10	0.83	1745	16	0.01	5	1032	14	<5	<20	182	<0.01	<10	25	<10	7	76
Standard:																													
PB113A		11.6	0.24	45	70	<5	1.64	34	2	<1	2215	1.11	<10	0.10	1526	64	0.01	1	100	5608	10	<20	86	0.01	<10	6	<10	1	7021

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
dl/n5739
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5741

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

6-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07214
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X10462	0.66	0.019
2	X10463	0.59	0.017
3	X10464	0.81	0.024
4	X10465	0.61	0.018
5	X10466	1.11	0.032
6	X10467	0.62	0.018
7	X10468	0.84	0.024
8	X10469	0.62	0.018
9	X10470	0.80	0.023
10	X10471	1.03	0.030
11	X10472	1.13	0.033
12	X10473	0.93	0.027
13	X10474	0.53	0.015
14	X10475	0.78	0.023
15	X10476	0.51	0.015
16	X10477	0.50	0.015
17	X10478	1.01	0.029
18	X10479	1.22	0.036
19	X10480	1.62	0.047
20	X10481	0.99	0.029
21	X10482	1.44	0.042
22	X10483	0.40	0.012
23	X10484	0.81	0.024
24	X10485	1.68	0.049
25	X10486	0.84	0.024
26	X10487	0.87	0.025
27	X10488	1.45	0.042
28	X10489	1.72	0.050
29	X10490	<0.03	<0.001

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5741 6-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X10491	1.05	0.031
31	X10492	1.08	0.031
32	X10493	0.35	0.010
33	X10494	0.45	0.013
34	X10495	0.51	0.015
35	X10496	0.72	0.021

QC DATA:

Repeat:

1	X10462	0.66	0.019
10	X10471	1.12	0.033
19	X10480	1.70	0.050
24	X10485	1.58	0.046
27	X10488	1.51	0.044

Resplits:

1	X10462	0.66	0.019

Standard:

SN26		8.58	0.250

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5741

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07214
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X10462	2.2	0.96	<5	50	<5	1.76	2	12	68	1682	3.60	<10	0.70	754	37	0.01	6	1310	36	10	<20	76	0.02	<10	31	<10	3	64
2	X10463	4.7	0.93	<5	45	<5	1.54	13	13	69	2280	3.92	<10	0.69	958	24	<0.01	5	1310	210	10	<20	54	0.03	<10	24	<10	3	887
3	X10464	3.2	0.99	<5	35	<5	1.26	2	16	81	2149	4.32	<10	0.75	1030	26	0.01	7	1340	82	10	<20	42	0.02	<10	28	<10	2	137
4	X10465	2.2	1.16	5	55	<5	1.13	2	13	70	1786	3.65	<10	0.92	736	43	<0.01	6	1350	64	15	<20	63	0.02	<10	30	<10	3	117
5	X10466	4.2	0.84	5	45	<5	1.37	2	15	99	3099	4.28	<10	0.58	695	24	<0.01	7	1040	66	10	<20	52	0.02	<10	20	<10	2	71
6	X10467	2.5	0.93	<5	40	<5	1.55	2	13	60	1798	3.59	<10	0.73	911	23	0.01	6	1170	44	15	<20	71	0.02	<10	25	<10	3	78
7	X10468	2.9	0.95	<5	60	<5	1.70	2	13	74	1743	3.19	<10	0.65	1010	28	0.02	5	1440	42	10	<20	83	0.02	<10	35	<10	4	74
8	X10469	2.2	0.87	<5	65	<5	2.59	1	13	63	1430	3.19	<10	0.55	1311	23	0.02	4	1440	40	5	<20	100	0.03	<10	29	<10	4	59
9	X10470	2.3	0.99	<5	75	<5	1.35	2	12	81	1808	4.23	<10	0.75	780	34	0.03	6	1190	36	10	<20	96	0.02	<10	44	<10	2	64
10	X10471	3.1	0.97	<5	45	<5	0.77	2	10	96	2828	3.77	<10	0.77	566	23	0.02	5	1030	42	10	<20	58	0.02	<10	30	<10	1	58
11	X10472	3.0	0.81	<5	45	<5	1.10	2	16	98	2479	4.20	<10	0.67	688	26	0.01	9	1270	42	20	<20	60	0.02	<10	22	<10	4	61
12	X10473	2.2	1.41	<5	55	<5	0.97	2	13	82	1801	4.04	<10	1.24	785	22	0.02	6	1240	42	15	<20	55	0.03	<10	35	<10	3	150
13	X10474	3.0	0.42	<5	40	<5	1.21	1	13	129	2390	3.69	<10	0.30	688	16	<0.01	5	870	46	<5	<20	50	0.02	<10	12	<10	3	26
14	X10475	2.8	0.83	<5	45	<5	0.82	2	13	96	2312	4.67	<10	0.65	596	21	<0.01	7	1090	56	10	<20	42	0.02	<10	19	<10	3	111
15	X10476	4.1	0.34	<5	45	<5	0.60	2	13	160	3233	4.24	<10	0.20	629	14	<0.01	8	600	40	5	<20	30	0.02	<10	9	<10	<1	64
16	X10477	2.7	0.39	10	45	<5	1.00	2	13	79	2711	3.55	<10	0.31	856	15	<0.01	4	1110	48	<5	<20	42	0.02	<10	10	<10	3	113
17	X10478	3.1	0.41	<5	55	<5	0.99	5	17	126	2800	7.84	<10	0.27	836	17	<0.01	10	890	40	<5	<20	40	0.03	<10	11	<10	<1	115
18	X10479	3.3	0.35	<5	45	<5	1.29	2	14	115	3670	4.59	<10	0.30	957	16	<0.01	7	800	32	10	<20	46	0.02	<10	10	<10	2	44
19	X10480	3.7	0.31	<5	50	<5	1.80	2	16	138	4370	4.84	<10	0.24	756	11	0.01	8	760	28	<5	<20	91	0.02	<10	11	<10	2	45
20	X10481	3.6	1.20	60	65	<5	0.74	4	17	61	3292	3.97	20	0.53	270	207	0.03	13	430	148	40	<20	38	0.04	<10	45	<10	6	159
21	X10482	1.9	0.56	<5	50	<5	2.11	<1	12	90	2225	4.08	<10	0.68	1188	17	<0.01	4	1070	24	<5	<20	95	0.03	<10	15	<10	4	66
22	X10483	2.7	0.33	<5	60	<5	0.82	5	28	169	2173	8.53	<10	0.11	501	20	<0.01	13	640	118	30	<20	41	0.03	<10	9	<10	<1	97
23	X10484	2.4	0.30	<5	45	<5	1.25	2	13	94	2992	3.88	<10	0.22	728	23	<0.01	4	740	60	5	<20	61	0.02	<10	7	<10	2	48
24	X10485	3.0	0.47	<5	45	<5	1.30	2	15	127	3332	4.14	<10	0.31	866	16	<0.01	5	770	44	<5	<20	49	0.02	<10	10	<10	3	53
25	X10486	2.4	0.57	<5	40	<5	1.01	1	14	85	2027	3.56	<10	0.38	688	25	<0.01	4	920	42	<5	<20	42	0.02	<10	10	<10	3	68

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X10487	4.3	0.41	<5	45	<5	1.28	2	15	140	3714	4.66	<10	0.33	806	21	<0.01	5	620	92	<5	<20	57	0.02	<10	9	<10	2	100
27	X10488	2.8	0.95	<5	45	<5	1.26	1	15	89	3103	4.81	<10	0.63	806	18	<0.01	5	840	42	10	<20	64	0.03	<10	15	<10	2	96
28	X10489	3.3	1.11	10	40	<5	1.19	3	15	107	3251	3.94	<10	0.70	715	34	<0.01	6	930	60	20	<20	62	0.01	<10	15	<10	3	107
29	X10490	<0.2	0.02	25	<5	5	>10	<1	2	5	8	0.03	<10	2.17	33	<1	<0.01	1	60	10	20	<20	6312	<0.01	<10	3	<10	<1	<1
30	X10491	2.4	0.80	<5	50	<5	1.42	2	12	85	2573	3.85	<10	0.61	752	28	<0.01	3	740	48	10	<20	77	0.02	<10	13	<10	3	76
31	X10492	4.9	0.41	<5	35	<5	1.17	2	18	114	5482	4.54	<10	0.27	611	13	<0.01	5	540	52	5	<20	54	0.02	<10	8	<10	<1	37
32	X10493	3.5	0.30	<5	40	<5	1.18	3	16	93	2945	5.87	<10	0.30	625	13	<0.01	5	680	84	10	<20	52	0.03	<10	7	<10	<1	92
33	X10494	2.8	0.37	<5	45	<5	1.21	4	11	116	3140	4.26	<10	0.32	762	15	<0.01	9	830	44	20	<20	57	<0.01	<10	10	<10	1	82
34	X10495	2.5	0.68	<5	40	<5	0.81	3	11	84	2114	3.75	<10	0.43	601	21	<0.01	4	1010	44	<5	<20	41	0.02	<10	9	<10	4	186
35	X10496	3.2	0.73	<5	45	<5	1.07	2	10	116	1793	4.56	<10	0.43	797	16	0.01	5	970	108	5	<20	53	0.03	<10	11	<10	2	168
QC DATA:																													
Repeat:																													
1	X10462	2.1	0.96	<5	50	<5	1.78	<1	13	69	1722	3.61	<10	0.71	766	35	0.02	5	1340	38	5	<20	91	0.03	<10	30	<10	6	65
10	X10471	3.0	0.97	5	55	<5	0.76	2	11	95	2803	3.80	<10	0.78	564	25	0.02	5	1020	44	15	<20	67	0.02	<10	31	<10	3	58
19	X10480	3.8	0.31	<5	45	<5	1.85	2	16	136	4300	4.78	<10	0.23	748	12	0.01	6	750	26	<5	<20	82	0.02	<10	11	<10	1	45
Resplit:																													
1	X10462	2.2	1.00	5	60	<5	1.70	1	12	76	1550	3.68	<10	0.72	696	35	0.01	6	1400	40	15	<20	81	0.02	<10	33	<10	4	65
Standard:																													
PB113A		11.4	0.23	45	65	<5	1.65	35	3	6	2213	1.04	<10	0.10	1478	62	0.02	2	100	5542	20	<20	85	0.02	<10	7	<10	<1	6921

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5741S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5742

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

6-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07225
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X12386	0.86	0.025
2	X12387	1.37	0.040
3	X12388	0.89	0.026
4	X12389	1.38	0.040
5	X12390	1.14	0.033
6	X12391	1.25	0.036
7	X12392	0.75	0.022
8	X12393	0.61	0.018
9	X12394	0.73	0.021
10	X12395	0.56	0.016
11	X12396	1.28	0.037
12	X12397	0.73	0.021
13	X12398	0.59	0.017
14	X12399	0.61	0.018
15	X12400	0.73	0.021
16	X12401	0.56	0.016
17	X12402	1.00	0.029
18	X12403	0.95	0.028
19	X12404	0.72	0.021
20	X12405	1.84	0.054
21	X12406	0.58	0.017
22	X12407	0.88	0.026
23	X12408	0.75	0.022
24	X12409	1.02	0.030
25	X12410	0.78	0.023
26	X12411	<0.03	<0.001
27	X12412	1.29	0.038
28	X12413	1.45	0.042
29	X12414	1.03	0.030

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5742 6-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X12415	1.13	0.033
31	X12416	0.84	0.024
32	X12417	0.50	0.015
33	X12418	0.68	0.020
34	X12419	1.48	0.043
35	X12420	1.13	0.033
QC DATA:			
Repeat:			
1	X12386	0.81	0.024
10	X12395	0.52	0.015
19	X12404	0.67	0.020
Resplits:			
1	X12386	0.93	0.027
Standard:			
SN26		8.54	0.249

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

6-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AS 2007- 5742

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07225
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X12386	3.0	0.72	20	50	<5	2.44	3	12	76	2661	4.63	<10	0.42	1209	10	<0.01	<1	726	26	<5	<20	145	<0.01	<10	7	<10	5	79
2	X12387	4.9	0.30	20	45	<5	2.67	10	11	125	3382	5.33	<10	0.08	1387	9	<0.01	<1	540	102	<5	<20	174	<0.01	<10	4	<10	4	222
3	X12388	2.8	0.50	15	45	<5	1.70	7	10	127	2210	4.95	<10	0.23	883	14	<0.01	1	606	100	<5	<20	131	<0.01	<10	7	<10	4	185
4	X12389	4.6	0.47	25	45	<5	1.27	4	9	147	4022	5.32	<10	0.21	730	12	<0.01	1	534	30	5	<20	93	<0.01	<10	7	<10	3	37
5	X12390	2.7	0.39	15	40	<5	1.43	4	12	126	2785	5.24	<10	0.18	927	12	<0.01	1	624	48	<5	<20	92	<0.01	<10	5	<10	4	61
6	X12391	4.5	0.31	20	50	<5	1.07	3	12	141	3617	6.07	<10	0.07	558	11	<0.01	<1	480	30	<5	<20	84	<0.01	<10	4	<10	4	14
7	X12392	2.6	0.79	15	45	<5	0.82	3	10	108	2525	4.93	<10	0.41	559	10	<0.01	<1	600	16	<5	<20	69	<0.01	<10	12	<10	4	73
8	X12393	2.4	0.73	15	50	<5	1.02	3	10	123	2372	4.38	<10	0.42	674	14	0.01	1	630	28	<5	<20	93	<0.01	<10	13	<10	4	62
9	X12394	2.2	0.96	10	65	<5	1.16	3	7	126	2021	4.54	<10	0.60	608	11	0.02	2	642	22	<5	<20	114	<0.01	<10	21	<10	3	63
10	X12395	3.8	0.39	35	40	<5	1.34	5	11	125	2915	4.86	<10	0.19	562	12	<0.01	<1	546	70	10	<20	99	<0.01	<10	6	<10	3	129
11	X12396	4.1	0.53	10	55	<5	2.60	3	12	105	3601	4.62	<10	0.46	899	12	0.01	1	588	30	<5	<20	218	<0.01	<10	12	<10	5	59
12	X12397	2.3	0.75	35	45	<5	1.06	5	9	128	1562	4.93	<10	0.33	683	10	<0.01	2	714	36	<5	<20	51	<0.01	<10	8	<10	4	158
13	X12398	3.4	0.30	20	40	<5	1.60	5	13	179	3514	5.70	<10	0.16	839	10	<0.01	2	504	86	<5	<20	108	<0.01	<10	4	<10	3	64
14	X12399	2.1	0.86	15	65	<5	1.89	3	9	152	2006	4.18	<10	0.51	1343	19	<0.01	2	666	24	<5	<20	117	<0.01	<10	11	<10	5	53
15	X12400	2.5	0.89	20	70	<5	2.21	3	13	128	2402	4.21	<10	0.57	1551	30	<0.01	2	654	20	<5	<20	136	<0.01	<10	10	<10	4	57
16	X12401	2.0	0.81	25	50	<5	1.30	4	10	106	1533	4.23	<10	0.44	1104	11	<0.01	2	684	42	<5	<20	90	<0.01	<10	9	<10	4	71
17	X12402	4.2	0.31	85	40	<5	0.79	4	11	177	3100	5.30	<10	0.05	675	12	<0.01	2	570	28	20	<20	57	<0.01	<10	4	<10	3	56
18	X12403	4.9	0.29	50	40	<5	0.63	3	11	177	3818	5.63	<10	0.02	268	11	<0.01	2	546	38	10	<20	48	<0.01	<10	4	<10	2	24
19	X12404	0.4	0.48	20	45	<5	0.73	3	12	179	3455	4.84	<10	0.13	608	13	<0.01	3	618	40	<5	<20	49	<0.01	<10	5	<10	3	43
20	X12405	3.9	1.18	45	55	<5	1.10	4	24	58	8574	4.24	20	0.63	212	603	0.03	61	390	60	25	<20	71	0.05	<10	40	<10	8	84
21	X12406	3.5	0.79	25	40	<5	0.40	3	16	195	3721	5.52	<10	0.19	527	17	<0.01	3	576	20	<5	<20	25	<0.01	<10	7	<10	3	55
22	X12407	3.4	0.47	35	40	<5	0.26	3	15	194	3754	5.64	<10	0.07	176	11	<0.01	3	666	16	<5	<20	15	<0.01	<10	5	<10	3	23
23	X12408	3.4	0.34	30	35	<5	0.33	4	12	200	3178	5.85	<10	0.05	395	12	<0.01	2	594	68	<5	<20	18	<0.01	<10	3	<10	2	71
24	X12409	4.2	0.36	30	40	<5	0.36	5	11	188	4469	6.41	<10	0.03	294	16	<0.01	2	618	40	10	<20	24	<0.01	<10	4	<10	2	103
25	X12410	5.4	0.84	25	40	<5	0.26	4	11	183	2564	5.36	<10	0.21	533	15	<0.01	2	630	32	5	<20	14	<0.01	<10	7	<10	3	102

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X12411	<0.2	0.02	<5	<5	<5	>10	<1	<1	2	4	0.03	<10	1.29	42	<1	<0.01	<1	18	<2	<5	<20	6953	<0.01	<10	<1	<10	<1	1
27	X12412	5.1	0.47	30	45	<5	1.45	4	13	170	2987	6.49	<10	0.30	1523	11	<0.01	2	642	20	5	<20	75	<0.01	<10	6	<10	3	46
28	X12413	3.6	0.26	20	40	<5	0.70	4	9	193	4600	5.81	<10	0.06	599	15	<0.01	2	438	30	5	<20	47	<0.01	<10	3	<10	2	47
29	X12414	4.2	0.67	20	45	<5	1.30	3	10	180	3551	5.20	<10	0.31	879	14	<0.01	2	516	36	<5	<20	94	<0.01	<10	7	<10	4	101
30	X12415	3.0	0.56	15	45	<5	1.14	3	10	230	3805	5.48	<10	0.21	766	17	<0.01	3	402	14	<5	<20	77	<0.01	<10	8	<10	2	50
31	X12416	2.2	0.51	10	45	<5	1.63	3	10	175	2792	5.62	<10	0.29	1066	16	<0.01	2	474	22	<5	<20	103	<0.01	<10	7	<10	3	58
32	X12417	2.3	0.42	15	40	<5	1.43	5	12	158	2731	5.58	<10	0.18	747	13	<0.01	<1	534	28	<5	<20	98	<0.01	<10	5	<10	3	103
33	X12418	2.2	0.64	15	45	<5	1.49	3	12	187	2790	5.21	<10	0.30	833	16	<0.01	2	552	20	<5	<20	88	<0.01	<10	7	<10	3	35
34	X12419	4.0	0.36	20	45	<5	0.93	6	14	180	4880	6.26	<10	0.17	777	15	<0.01	1	510	26	<5	<20	51	<0.01	<10	4	<10	2	67
35	X12420	3.8	0.87	20	50	<5	0.97	3	9	192	3484	5.46	<10	0.41	1132	11	<0.01	2	510	18	<5	<20	48	<0.01	<10	9	<10	2	78
QC DATA:																													
Repeat:																													
1	X12386	2.9	0.69	20	45	<5	2.25	3	11	72	2525	4.32	<10	0.39	1177	9	<0.01	<1	684	22	<5	<20	134	<0.01	<10	7	<10	5	73
10	X12395	3.5	0.40	40	40	<5	1.36	5	11	126	2984	5.00	<10	0.20	566	17	<0.01	<1	570	70	10	<20	99	<0.01	<10	6	<10	3	128
19	X12404	0.7	0.48	25	45	<5	0.68	3	12	177	3443	4.85	<10	0.14	599	14	<0.01	2	612	38	<5	<20	49	<0.01	<10	4	<10	3	41
Resplit:																													
1	X12386	2.7	0.70	20	50	<5	2.23	3	11	83	2616	4.56	<10	0.39	1186	11	<0.01	1	762	24	<5	<20	152	<0.01	<10	8	<10	5	75
Standard:																													
PB113A		11.0	0.23	55	70	<5	1.69	30	2	<1	2305	1.08	<10	0.10	1534	69	0.01	1	90	5586	10	<20	87	0.01	<10	6	<10	1	7147

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/jl
df/N5739
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5743

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

6-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07202
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X14036	0.72	0.021
2	X14037	0.44	0.013
3	X14038	0.93	0.027
4	X14039	1.02	0.030
5	X14040	0.82	0.024
6	X14041	0.73	0.021
7	X14042	0.49	0.014
8	X14043	0.55	0.016
9	X14044	0.48	0.014
10	X14045	0.45	0.013
11	X14046	0.85	0.025
12	X14047	0.90	0.026
13	X14048	0.51	0.015
14	X14049	0.66	0.019
15	X14050	1.01	0.029
16	X14051	0.85	0.025
17	X14052	0.58	0.017
18	X14053	0.89	0.026
19	X14054	0.87	0.025
20	X14055	1.14	0.033
21	X14056	1.47	0.043
22	X14057	1.57	0.046
23	X14058	1.12	0.033
24	X14059	1.23	0.036
25	X14060	1.06	0.031
26	X14061	0.84	0.024
27	X14062	0.99	0.029
28	X14063	0.81	0.024
29	X14064	1.87	0.055

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5743 6-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X14065	0.85	0.025
31	X14066	0.82	0.024
32	X14067	<0.03	<0.001
33	X14068	0.86	0.025
34	X14069	0.63	0.018
35	X14070	0.86	0.025

QC DATA:

Repeat:

1	X14036	0.67	0.020
3	X14038	0.87	0.025
10	X14045	0.42	0.012
19	X14054	0.85	0.025
21	X14056	1.55	0.045
22	X14057	1.48	0.043

Resplits:

1	X14036	0.77	0.022

Standard:

SN26		8.50	0.248

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

5-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5743

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07202
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X14036	2.0	0.47	15	55	<5	1.02	2	14	124	1549	4.72	<10	0.56	1366	49	<0.01	16	570	144	<5	<20	74	0.05	<10	5	<10	2	183
2	X14037	1.6	0.30	<5	35	<5	0.33	4	11	144	1391	3.34	<10	0.20	455	66	<0.01	11	230	86	<5	<20	34	0.02	<10	4	<10	<1	281
3	X14038	1.9	0.47	10	35	<5	0.31	3	12	131	1626	3.91	<10	0.33	443	88	<0.01	18	390	44	<5	<20	26	0.02	<10	7	<10	<1	231
4	X14039	2.9	0.28	15	55	<5	0.28	6	13	148	2123	4.66	<10	0.09	274	61	0.01	24	630	86	<5	<20	46	0.02	<10	7	<10	<1	371
5	X14040	1.4	0.28	20	40	<5	0.32	2	11	145	1337	3.91	<10	0.10	119	78	0.01	34	520	58	<5	<20	55	0.02	<10	6	<10	<1	182
6	X14041	1.3	0.36	20	40	<5	0.19	2	12	168	1636	4.25	<10	0.17	201	135	0.01	27	420	52	5	<20	29	0.02	<10	7	<10	<1	121
7	X14042	1.5	0.19	75	40	<5	0.15	2	10	135	1629	4.09	<10	<0.01	67	103	0.01	15	450	42	20	<20	22	0.02	<10	3	<10	<1	69
8	X14043	1.1	0.20	40	40	<5	0.16	2	10	141	1435	3.89	<10	0.05	99	102	<0.01	18	360	42	10	<20	27	<0.01	<10	4	<10	<1	91
9	X14044	1.6	0.21	45	40	<5	0.23	3	11	144	1053	5.09	<10	<0.01	94	117	<0.01	16	830	72	<5	<20	27	0.02	<10	4	<10	<1	177
10	X14045	1.5	0.24	15	40	<5	0.15	3	9	147	1243	3.48	<10	0.11	168	100	<0.01	14	280	170	<5	<20	34	0.02	<10	4	<10	<1	308
11	X14046	1.9	0.25	20	35	<5	0.19	2	9	156	1700	3.69	<10	0.11	205	123	<0.01	14	380	62	<5	<20	30	0.01	<10	5	<10	<1	156
12	X14047	2.3	0.36	15	35	<5	0.67	4	15	122	1644	4.36	<10	0.35	947	134	<0.01	10	850	88	10	<20	40	0.02	<10	8	<10	<1	227
13	X14048	2.1	0.47	15	50	<5	0.81	3	13	86	1354	3.72	<10	0.50	1066	75	0.01	7	1050	94	10	<20	59	0.03	<10	9	<10	2	230
14	X14049	1.8	0.73	5	45	<5	0.86	3	14	96	1184	4.66	<10	0.73	1456	71	0.01	8	1070	82	5	<20	48	0.03	<10	12	<10	2	262
15	X14050	2.4	0.77	5	45	<5	0.78	3	14	108	1441	4.83	<10	0.71	1567	113	0.01	8	1010	76	10	<20	49	0.03	<10	14	<10	<1	267
16	X14051	2.6	0.44	10	45	<5	0.47	4	14	104	1751	4.86	<10	0.28	739	54	0.01	9	1250	116	<5	<20	34	0.03	<10	10	<10	1	400
17	X14052	2.2	0.43	<5	55	<5	0.45	4	15	94	1577	5.50	<10	0.27	774	60	0.01	9	1140	102	<5	<20	44	0.03	<10	10	<10	<1	269
18	X14053	1.9	0.98	15	45	<5	0.65	2	17	87	1327	5.11	<10	0.84	1450	101	0.01	12	1360	62	15	<20	35	0.03	<10	20	<10	1	197
19	X14054	1.8	0.99	<5	45	<5	0.66	2	15	97	1253	4.91	<10	0.86	1516	101	0.02	10	1310	68	10	<20	38	0.04	<10	19	<10	1	217
20	X14055	2.3	0.50	5	35	<5	0.55	3	17	103	1670	5.34	<10	0.40	991	52	0.02	15	1020	62	<5	<20	32	0.03	<10	12	<10	<1	159
21	X14056	2.9	0.77	10	45	<5	0.29	<1	15	124	2033	5.14	<10	0.59	602	52	0.01	17	520	56	<5	<20	37	0.03	<10	11	<10	<1	209
22	X14057	3.0	1.19	<5	30	<5	0.27	2	18	105	2277	5.53	<10	0.92	776	74	0.01	17	580	56	10	<20	23	0.03	<10	21	<10	<1	280
23	X14058	2.4	0.47	<5	40	<5	0.32	4	14	132	1786	4.55	<10	0.31	304	80	0.01	14	660	78	<5	<20	44	0.02	<10	9	<10	<1	281
24	X14059	2.7	0.60	20	45	<5	0.36	2	14	111	2048	4.55	<10	0.43	434	60	0.01	18	660	90	10	<20	53	0.02	<10	9	<10	<1	251
25	X14060	2.5	0.56	<5	45	<5	0.25	3	20	119	1850	5.50	<10	0.29	379	65	0.01	10	940	100	<5	<20	43	0.02	<10	12	<10	<1	232

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X14061	2.1	0.71	<5	45	<5	0.30	2	15	108	1353	4.80	<10	0.40	644	57	0.01	5	1230	92	<5	<20	42	0.02	<10	16	<10	<1	230
27	X14062	2.6	0.48	5	45	<5	0.27	3	18	90	1636	5.59	<10	0.15	281	117	0.01	6	1050	104	<5	<20	32	0.02	<10	12	<10	<1	212
28	X14063	2.2	0.61	<5	35	<5	0.34	2	14	100	1118	5.02	<10	0.31	428	62	0.01	6	1430	78	<5	<20	33	0.03	<10	14	<10	<1	199
29	X14064	3.9	0.99	30	60	<5	1.01	4	22	53	8548	4.08	10	0.64	198	577	0.04	63	160	76	45	<20	73	0.02	<10	43	<10	7	75
30	X14065	2.0	0.59	10	45	<5	0.27	<1	18	123	1429	5.09	<10	0.28	368	48	0.01	6	1050	86	<5	<20	46	0.03	<10	14	<10	<1	117
31	X14066	3.3	0.40	50	40	<5	0.30	4	15	109	1963	4.82	<10	0.16	220	75	0.01	8	1100	86	30	<20	43	0.01	<10	9	<10	<1	173
32	X14067	<0.2	0.02	25	<5	5	>10	<1	1	3	5	0.03	<10	1.71	23	<1	<0.01	<1	50	8	10	<20	6734	<0.01	<10	2	<10	<1	<1
33	X14068	2.8	0.38	205	50	<5	0.34	5	18	114	1689	5.07	<10	0.15	219	101	0.02	7	940	148	65	<20	69	0.02	<10	9	<10	1	207
34	X14069	2.2	0.40	40	45	<5	0.51	4	16	114	1617	4.67	<10	0.13	216	160	0.02	7	2130	158	10	<20	57	0.02	<10	9	<10	3	302
35	X14070	2.2	0.57	10	50	<5	0.26	6	16	109	1627	5.44	<10	0.31	317	64	0.02	8	970	92	<5	<20	36	0.02	<10	13	<10	<1	317
QC DATA:																													
Repeat:																													
1	X14036	1.9	0.50	15	50	<5	1.05	3	14	128	1604	4.77	<10	0.60	1397	44	<0.01	18	590	144	5	<20	69	0.03	<10	7	<10	1	183
10	X14045	1.5	0.25	25	45	<5	0.15	4	9	150	1280	3.54	<10	0.12	172	103	<0.01	16	290	172	5	<20	30	<0.01	<10	5	<10	<1	309
19	X14054	1.8	1.00	5	40	<5	0.66	3	15	97	1260	4.94	<10	0.86	1524	89	0.01	11	1340	64	10	<20	36	0.03	<10	19	<10	<1	219
Resplit:																													
1	X14036	1.9	0.52	10	55	<5	0.99	2	16	125	1614	5.22	<10	0.52	1275	50	<0.01	19	640	130	5	<20	69	0.03	<10	7	<10	2	175
Standard:																													
PB113A		11.6	0.24	45	50	<5	1.68	37	3	6	2218	1.05	<10	0.12	1450	66	0.01	3	90	5408	20	<20	82	0.02	<10	8	<10	<1	6958

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5741S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5744

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

6-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07198
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05693	0.41	0.012
2	X05694	0.52	0.015
3	X05695	0.40	0.012
4	X05696	<0.03	<0.001
5	X05697	0.49	0.014
6	X05698	0.45	0.013
7	X05699	0.83	0.024
8	X05700	0.55	0.016
9	X05701	1.23	0.036
10	X05702	0.83	0.024
11	X05703	2.21	0.064
12	X05704	1.45	0.042
13	X05705	0.93	0.027
14	X05706	0.54	0.016
15	X05707	0.34	0.010
16	X05708	0.19	0.006
17	X05709	0.65	0.019
18	X05710	0.79	0.023
19	X05711	1.45	0.042
20	X05712	0.37	0.011
21	X05713	0.42	0.012
22	X05714	0.34	0.010
23	X05715	0.63	0.018
24	X05716	0.07	0.002
25	X05717	0.84	0.024
26	X05718	0.60	0.017
27	X05719	0.50	0.015
28	X05720	0.54	0.016
29	X05721	0.38	0.011

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5744 6-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X05722	0.38	0.011
31	X05723	0.41	0.012
32	X05724	0.29	0.008
33	X05725	0.56	0.016
34	X05726	0.48	0.014
35	X05727	0.35	0.010
QC DATA:			
Repeat:			
1	X05693	0.41	0.012
10	X05702	0.73	0.021
11	X05703	2.34	0.068
12	X05704	1.36	0.040
19	X05711	1.56	0.045
Resplits:			
1	X05693	0.39	0.011
Standard:			
SN26		8.62	0.251

AU: 30g FA/AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
XLS/07

5 Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250 .73-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5744

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07198
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05693	1.0	1.17	15	215	<5	2.89	2	13	77	1186	4.66	<10	1.02	1394	13	0.02	6	1260	42	20	<20	213	0.04	<10	72	<10	7	94
2	X05694	3.3	1.39	25	110	<5	2.65	2	14	99	1600	4.23	<10	1.27	1452	14	0.02	6	1200	44	20	<20	252	0.04	<10	70	<10	6	91
3	X05695	1.1	1.09	20	140	<5	3.21	2	14	75	1039	4.09	<10	0.82	1416	19	0.02	7	1260	34	20	<20	257	0.03	<10	52	<10	5	81
4	X05696	<0.2	0.03	40	<5	<5	>10	<1	2	3	5	0.04	<10	1.92	30	1	<0.01	3	70	12	30	<20	6813	<0.01	<10	6	<10	1	<1
5	X05697	1.4	1.07	15	130	<5	2.52	<1	11	95	1374	3.65	<10	0.79	1145	11	0.01	4	1080	36	<5	<20	192	0.03	<10	39	<10	4	75
6	X05698	1.5	1.39	20	140	<5	2.46	1	11	86	1608	3.97	<10	1.11	1221	14	0.01	6	1220	40	15	<20	182	0.03	<10	47	<10	5	94
7	X05699	4.1	1.34	35	45	<5	3.14	2	15	116	3583	4.05	<10	0.97	1486	13	0.01	7	1210	100	15	<20	182	0.03	<10	31	<10	4	157
8	X05700	1.8	1.43	35	70	<5	3.58	2	14	78	1189	4.52	<10	1.02	1591	20	<0.01	6	1380	50	15	<20	240	0.04	<10	39	<10	3	132
9	X05701	2.8	1.11	45	50	<5	3.77	1	13	103	1517	3.80	<10	0.67	1436	15	<0.01	5	1070	46	5	<20	243	0.03	<10	22	<10	4	89
10	X05702	3.1	0.37	50	35	<5	1.69	2	11	93	1426	5.12	<10	0.10	1168	16	<0.01	5	760	80	<5	<20	154	0.03	<10	13	<10	1	30
11	X05703	5.0	0.52	65	50	<5	1.61	4	27	167	4076	5.75	<10	0.21	956	12	<0.01	7	600	52	<5	<20	160	0.04	<10	15	<10	6	61
12	X05704	2.0	0.78	45	50	<5	1.41	1	13	131	1019	4.12	<10	0.41	642	14	<0.01	4	640	44	5	<20	101	0.03	<10	19	<10	3	61
13	X05705	1.7	0.72	45	50	<5	1.70	2	14	110	1004	4.44	<10	0.39	728	13	<0.01	4	580	40	<5	<20	128	0.03	<10	21	<10	4	59
14	X05706	1.7	1.00	20	110	<5	1.99	1	11	93	1364	4.79	<10	0.59	867	15	<0.01	4	890	34	5	<20	139	0.03	<10	45	<10	4	91
15	X05707	1.2	1.03	15	200	<5	2.24	2	11	123	1064	5.76	<10	0.66	994	12	0.02	6	710	38	10	<20	186	0.03	<10	84	<10	2	104
16	X05708	0.7	0.88	10	215	<5	1.94	2	10	82	705	4.91	<10	0.49	789	13	0.02	4	990	38	10	<20	162	0.03	<10	57	<10	4	79
17	X05709	2.0	0.97	15	145	<5	1.98	2	13	118	2102	5.00	<10	0.55	839	11	0.02	4	820	46	5	<20	188	0.04	<10	55	<10	6	89
18	X05710	3.5	0.96	30	65	<5	1.14	3	14	118	3075	4.02	<10	0.63	690	17	0.01	10	560	50	35	<20	102	<0.01	<10	32	<10	5	94
19	X05711	3.7	0.97	15	60	<5	1.39	1	17	136	3143	6.33	<10	0.60	737	11	0.01	7	480	36	<5	<20	116	0.04	<10	76	<10	3	87
20	X05712	1.7	0.88	10	75	<5	1.39	2	12	114	1429	4.51	<10	0.54	635	14	<0.01	5	650	44	<5	<20	110	0.03	<10	43	<10	4	102
21	X05713	1.4	0.88	30	160	<5	1.63	1	9	186	1292	4.11	<10	0.47	672	12	<0.01	6	600	42	5	<20	117	0.03	<10	40	<10	4	95
22	X05714	1.5	1.02	15	110	<5	2.15	<1	9	110	1118	3.92	<10	0.62	875	15	<0.01	5	650	34	10	<20	122	0.03	<10	34	<10	4	76
23	X05715	3.4	1.18	30	80	<5	1.55	1	11	142	2294	5.28	<10	0.73	819	10	<0.01	6	560	38	10	<20	105	0.04	<10	62	<10	4	92
24	X05716	<0.2	0.91	70	175	5	0.32	3	80	291	441	>10	10	0.20	446	124	0.05	421	200	116	<5	<20	15	0.07	<10	30	<10	<1	418
25	X05717	3.0	1.17	40	65	<5	2.04	2	14	111	2120	5.74	<10	0.70	1094	15	<0.01	8	500	44	15	<20	132	0.04	<10	57	<10	3	91

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05718	2.6	1.07	30	70	<5	2.69	3	15	121	1956	5.53	<10	0.64	1042	15	0.01	8	880	50	25	<20	170	0.04	<10	57	<10	4	96
27	X05719	1.8	1.10	20	115	<5	2.32	1	11	90	1285	4.98	<10	0.63	855	15	<0.01	6	1000	40	15	<20	152	0.04	<10	43	<10	5	85
28	X05720	1.1	1.27	30	60	<5	1.20	1	14	104	700	4.01	<10	0.75	664	11	<0.01	5	890	44	10	<20	71	0.03	<10	24	<10	5	88
29	X05721	2.0	1.23	40	60	<5	1.06	1	11	82	908	3.93	<10	0.75	660	13	<0.01	5	930	50	10	<20	67	0.03	<10	22	<10	5	94
30	X05722	4.8	1.50	40	60	<5	3.04	1	11	103	1665	4.29	<10	1.17	1340	11	0.01	4	850	62	15	<20	110	0.04	<10	28	<10	6	89
31	X05723	2.1	1.29	45	50	<5	1.71	<1	11	93	1230	4.26	<10	0.82	872	13	<0.01	6	770	48	15	<20	67	0.03	<10	22	<10	5	82
32	X05724	1.2	1.15	35	50	<5	1.18	<1	9	98	975	3.37	<10	0.70	736	9	<0.01	4	840	40	10	<20	75	0.03	<10	22	<10	5	87
33	X05725	2.1	0.90	25	125	<5	1.71	<1	10	83	1925	3.37	<10	0.48	691	11	0.01	6	800	48	10	<20	143	0.04	<10	31	<10	7	66
34	X05726	1.9	0.79	15	145	<5	1.77	<1	10	106	1659	3.26	<10	0.39	678	9	<0.01	4	770	46	10	<20	146	0.04	<10	30	<10	6	63
35	X05727	1.5	0.97	25	80	<5	1.48	<1	9	98	1211	3.36	<10	0.56	677	10	<0.01	4	860	34	10	<20	102	0.04	<10	27	<10	5	67
QC DATA:																													
Repeat:																													
1	X05693	1.1	1.20	10	210	<5	2.95	1	13	77	1207	4.78	<10	1.04	1429	14	0.02	5	1280	40	15	<20	216	0.04	<10	72	<10	4	96
10	X05702	3.4	0.39	50	35	<5	1.76	3	12	95	1412	5.10	<10	0.11	1162	17	<0.01	6	760	82	5	<20	168	0.03	<10	13	<10	3	31
19	X05711	3.5	0.98	10	60	<5	1.39	2	17	138	3126	6.36	<10	0.61	737	12	0.01	9	480	36	<5	<20	122	0.03	<10	78	<10	2	88
Resplit:																													
1	X05693	1.0	1.25	10	215	<5	2.92	2	12	80	1186	4.84	<10	1.06	1444	14	0.03	7	1280	42	15	<20	219	0.04	<10	77	<10	6	97
Standard:																													
PB113A		11.6	0.24	45	70	<5	1.68	37	3	7	2272	1.07	<10	0.14	1403	68	0.02	5	100	5412	20	<20	83	0.01	<10	12	<10	1	6986

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5741S
XLS/07

Eco Tech LABORATORY LTD.

ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AS 2007- 5745

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

6-Dec-07

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07200
Submitted by: Peter Erwich

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	X05763	0.38	0.011
2	X05764	0.31	0.009
3	X05765	1.12	0.033
4	X05766	<0.03	<0.001
5	X05767	0.50	0.015
6	X05768	0.32	0.009
7	X05769	1.82	0.053
8	X05770	0.45	0.013
9	X05771	0.41	0.012
10	X05772	0.49	0.014
11	X05773	0.39	0.011
12	X05774	0.30	0.009
13	X05775	0.16	0.005
14	X05776	0.48	0.014
15	X05777	0.23	0.007
16	X05778	0.38	0.011
17	X05779	0.25	0.007
18	X05780	0.14	0.004
19	X05781	0.18	0.005
20	X05782	0.80	0.023
21	X05783	0.55	0.016
22	X05784	0.34	0.010
23	X05785	0.36	0.010
24	X05786	0.39	0.011
25	X05787	0.36	0.010
26	X05788	0.35	0.010
27	X05789	0.32	0.009
28	X05790	0.50	0.015
29	X05791	0.36	0.010

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Seabridge Gold Inc. AS7-5745 6-Dec-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	X05792	0.28	0.008
31	X05793	0.26	0.008
32	X05794	0.27	0.008
33	X05795	0.26	0.008
34	X05796	0.21	0.006
35	X05797	0.50	0.015

QC DATA:

Repeat:

1	X05763	0.42	0.012
3	X05765	1.12	0.033
8	X05770	0.46	0.013
10	X05772	0.48	0.014
19	X05781	0.21	0.006

Resplits:

1	X05763	0.45	0.013

Standard:

SN26		8.46	0.247

AU: 30g FA/AA-Finish

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

5-Dec-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AS 2007-5745

Seabridge Gold Inc.
106 Front Street East, Suite 400
Toronto, Ontario
M5A 1E1

No. of samples received: 35
Sample Type: Core
Project: KSM
Shipment #: 07200
Submitted by: Peter Erwich

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X05763	2.6	0.90	30	60	<5	2.14	<1	10	91	2525	2.65	<10	0.51	665	25	0.02	5	970	44	15	<20	58	0.06	<10	20	<10	6	61
2	X05764	3.7	0.87	30	110	<5	2.26	<1	9	91	1500	1.88	<10	0.49	685	19	0.02	4	1050	38	10	<20	68	0.07	<10	21	<10	7	73
3	X05765	10.5	0.50	30	75	<5	2.19	1	12	139	7095	1.83	<10	0.27	444	11	0.02	5	320	62	10	<20	62	0.05	<10	12	<10	8	42
4	X05766	<0.2	0.03	55	<5	25	>10	<1	2	5	6	0.03	<10	2.06	30	<1	<0.01	<1	60	14	25	<20	6224	<0.01	<10	5	<10	2	1
5	X05767	5.7	0.88	30	65	<5	2.48	2	14	129	4435	2.22	<10	0.64	544	50	<0.01	13	600	52	10	<20	99	0.09	<10	18	<10	6	48
6	X05768	2.0	0.81	35	100	<5	2.91	<1	9	82	1275	2.09	<10	0.41	688	24	0.02	3	1020	40	15	<20	81	0.09	<10	23	<10	6	59
7	X05769	3.9	1.18	60	50	<5	1.06	2	23	54	8550	4.31	20	0.66	205	608	0.04	66	160	84	30	<20	57	0.05	<10	48	<10	5	75
8	X05770	2.7	0.89	40	90	<5	2.43	<1	10	101	1906	2.28	<10	0.46	792	79	0.01	4	970	38	10	<20	62	0.08	<10	20	<10	9	70
9	X05771	6.1	0.85	40	75	<5	3.03	2	10	114	1635	2.32	<10	0.44	1012	74	0.01	5	960	40	10	<20	69	0.07	<10	18	<10	7	100
10	X05772	6.0	0.82	45	50	<5	2.27	4	11	93	1866	2.64	<10	0.45	779	62	0.02	7	1090	86	25	<20	64	0.06	<10	24	<10	6	140
11	X05773	1.7	0.87	55	125	<5	1.84	<1	10	99	1380	2.61	<10	0.57	574	43	0.03	1	1020	58	<5	<20	102	0.11	<10	39	<10	9	222
12	X05774	1.1	0.98	30	70	<5	2.41	<1	10	126	1175	3.07	<10	0.59	663	28	0.03	5	960	40	5	<20	133	0.10	<10	39	<10	2	92
13	X05775	0.9	0.90	30	105	<5	2.45	<1	9	85	560	2.54	<10	0.56	668	35	0.03	4	1080	36	15	<20	171	0.10	<10	35	<10	6	82
14	X05776	2.5	0.80	35	85	<5	3.33	1	9	123	2571	2.17	<10	0.46	796	85	0.02	5	780	56	10	<20	83	0.09	<10	26	<10	8	103
15	X05777	1.2	0.79	30	155	<5	1.82	<1	9	133	1189	2.28	<10	0.45	470	21	0.03	4	900	42	5	<20	94	0.09	<10	31	<10	6	65
16	X05778	3.2	0.97	30	105	<5	2.08	5	11	100	1731	2.81	<10	0.61	699	92	0.03	4	1060	56	<5	<20	110	0.10	<10	34	<10	8	531
17	X05779	1.4	0.96	30	300	<5	2.43	<1	8	96	1318	2.61	<10	0.60	651	47	0.03	5	1140	38	15	<20	194	0.10	<10	39	<10	6	80
18	X05780	1.5	0.94	45	255	<5	2.26	<1	9	97	1544	2.82	<10	0.56	614	46	0.04	4	1040	42	10	<20	227	0.11	<10	43	<10	5	77
19	X05781	1.4	0.75	40	80	<5	4.46	1	8	61	682	2.27	<10	0.41	1570	38	0.02	3	1040	38	10	<20	131	0.08	<10	28	<10	7	69
20	X05782	2.7	0.92	35	60	<5	4.14	1	9	75	2120	2.22	<10	0.62	1412	71	0.03	5	950	42	15	<20	83	0.07	<10	31	<10	6	72
21	X05783	2.5	0.93	40	95	<5	3.70	1	10	69	2182	1.92	<10	0.62	940	208	0.02	2	1070	38	15	<20	92	0.07	<10	22	<10	8	79
22	X05784	2.2	1.05	30	105	<5	2.24	4	9	101	1715	2.45	<10	0.64	677	45	0.02	7	1090	50	20	<20	86	0.07	<10	31	<10	6	226
23	X05785	1.9	0.96	45	120	<5	1.93	<1	11	93	1422	2.86	<10	0.62	548	138	0.03	4	1090	50	5	<20	140	0.11	<10	40	<10	8	101
24	X05786	2.4	0.91	30	85	<5	2.68	<1	10	125	1077	2.76	<10	0.55	720	57	0.03	4	930	46	5	<20	121	0.08	<10	35	<10	5	84
25	X05787	2.3	0.90	30	100	<5	1.76	<1	10	118	1447	2.72	<10	0.54	579	32	0.02	4	830	36	5	<20	95	0.07	<10	31	<10	4	62

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X05788	1.3	0.94	35	280	<5	2.22	<1	8	111	987	2.81	<10	0.59	629	67	0.03	4	1060	40	5	<20	104	0.09	<10	35	<10	7	56
27	X05789	2.8	0.80	30	70	<5	4.30	<1	8	120	1204	2.38	<10	0.49	1247	38	0.02	4	770	52	10	<20	163	0.07	<10	28	<10	7	60
28	X05790	2.7	0.91	45	80	<5	2.46	<1	9	127	1467	2.03	<10	0.54	802	68	0.02	5	860	58	<5	<20	72	0.07	<10	20	<10	7	97
29	X05791	2.5	0.90	55	45	<5	2.70	5	10	117	1507	2.46	<10	0.59	803	113	0.02	3	870	80	10	<20	106	0.08	<10	28	<10	7	442
30	X05792	1.7	0.79	40	120	<5	2.33	<1	9	85	1206	2.24	<10	0.48	612	156	0.02	3	980	50	10	<20	88	0.08	<10	29	<10	7	74
31	X05793	2.1	0.78	35	65	<5	2.89	3	9	123	1185	2.10	<10	0.41	777	134	0.02	4	760	98	10	<20	97	0.06	<10	19	<10	6	147
32	X05794	1.5	0.84	40	145	<5	2.53	<1	9	93	1119	2.17	<10	0.45	739	153	0.02	3	920	52	5	<20	85	0.08	<10	24	<10	6	103
33	X05795	1.7	0.91	35	65	<5	3.07	5	11	103	1211	2.77	<10	0.45	856	33	0.02	6	1070	56	20	<20	86	0.05	<10	26	<10	7	236
34	X05796	1.7	0.80	50	40	<5	3.62	<1	10	106	823	2.23	<10	0.39	891	94	0.01	4	1040	32	10	<20	140	0.06	<10	18	<10	5	68
35	X05797	2.6	0.91	60	50	<5	3.41	4	10	134	1075	2.70	<10	0.50	919	106	0.02	4	950	104	5	<20	171	0.08	<10	25	<10	6	282
QC DATA:																													
Repeat:																													
1	X05763	2.6	0.95	25	60	<5	2.15	<1	10	93	2552	2.67	<10	0.51	668	26	0.02	4	930	40	10	<20	51	0.07	<10	21	<10	4	59
10	X05772	5.8	0.81	50	60	<5	2.21	3	11	90	1777	2.57	<10	0.41	751	60	0.02	3	1090	86	20	<20	69	0.07	<10	23	<10	7	138
19	X05781	1.4	0.77	35	80	<5	4.57	<1	9	61	688	2.31	<10	0.42	1597	37	0.02	3	1070	40	10	<20	136	0.09	<10	28	<10	7	70
Resplit:																													
1	X05763	2.6	0.89	35	65	<5	2.19	<1	9	95	2396	2.52	<10	0.49	675	24	0.02	4	1040	42	10	<20	58	0.07	<10	21	<10	5	60
Standard:																													
PB113A		10.9	0.30	65	60	<5	1.75	38	3	6	2208	1.09	<10	0.13	1440	89	0.01	3	100	5602	25	<20	90	0.02	<10	10	<10	<1	6891

ICP: Aqua Regia Digestion/ ICP-Finish
Ag: Aqua Regia Digestion/ AA-Finish

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

JJ/nl
df/5741S
XLS/07