

**Assessment Report**

**2007 Diamond Drilling; Silver Streak Project**

**Omineca Mining Division**

**NTS 93L/2**

**Latitude 54 deg 11 min North; Longitude 126 deg 45 min West**

**For: Cadillac Mining Corporation**

**By: Andre J. Audet P.Eng  
Courtenay, BC**

**July 21, 2008**

**Resubmitted December 2008**

## TABLE OF CONTENTS

INTRODUCTION.....	4
LOCATION AND ACCESS .....	4
TOPOGRAPHY, CLIMATE AND VEGETATION .....	4
TENURE .....	4
HISTORICAL EXPLORATION WORK.....	7
GEOLOGY .....	7
PROGRAM OBJECTIVES AND EXECUTION.....	7
STATEMENT OF COSTS.....	7
MINERALIZATION.....	7
RESULTS AND DISCUSSION.....	9
CONCLUSIONS AND RECOMMENDATIONS.....	9
BIBLIOGRAPHY.....	13
STATEMENT OF QUALIFICATIONS.....	14

## LIST OF TABLES

TABLE 1	CLAIMS AND OWNERSHIP	PAGE 1
TABLE 2	SUMMARY OF COSTS	PAGE 3
TABLE 3	SELECTED ANALYTICAL RESULTS	PAGE 5

## LIST OF FIGURES

FIGURE 1	LOCATION MAP	PAGE 2
FIGURE 2	CLAIM LOCATION MAP	PAGE 3
FIGURE 3	DRILLING AND TRENCHING PLAN	APPENDIX 1

## **APPENDICIES**

Appendix 1	Drilling and Trenching Plan
Appendix 2	Diamond Drill Logs and Analytical Data (as Excel files)
Appendix 3	Certificates of Analysis (as PDF files)

## INTRODUCTION

Cadillac Mining completed a four hole 549 m drilling program on the subject Silver Streak property between December 9, and December 16, 2007. The program was conducted to test the characteristics and extent of elevated silver mineralization identified previously in localized trenching and shallow drilling.

## LOCATION AND ACCESS

The Silver Streak property is located approximately 25km SW of Houston, B.C.; in North-central British Columbia. (Figure 1). The property is accessible via the Morice River road off Highway 16, 4 km west of Houston, then, at about 26.5km, south for 6km along the Carrier logging road.

## TOPOGRAPHY, CLIMATE AND VEGETATION


Topography is gently rolling generally with meandering streams numerous small lakes and localized swamps at about 2500m with occasional hills and ridges reaching 3000m and greater. Climate is moderate with warm generally dry summers with cold winter. Vegetation in the area has been completely burned over in 1983 and is partially regenerated with juvenile conifers.

## TENURE

The property is held under option from a group of prospectors as shown in the table below. A map of claims showing boundaries and location is presented in Figure 2

**Table 1 Claims and Ownership**


Owner	Claim Name	Tenure #	Area (hec)	Good to	Number of Cells
Gerald Westgarde	BIRD	566533	37.8	Sept 23, 2008	2
	ZOO	566788	37.8	Sep 27, 2008	2
	HAT	564827	75.6	Aug 19, 2008	4
	CARRIER 1	533152	113.5	April 27, 2008	6
	BUG	566465	56.7	Sept 21, 2008	3
	TEA	566521	37.8	Sept 22, 2008	2
Edward Westgarde	START	538876	113.5	August 8, 2008	6
	SHARP	538877	37.8	August 8, 2008	2
Barry Hofsink	SILVER STREAK	532613	94.5	April 19, 2008	5



**Figure 1**

*Silver Streak Project*

**British Columbia Canada**



## **HISTORICAL EXPLORATION WORK**

The Silver Streak prospect was initially staked in 1989 following the discovery of significant silver and copper mineralization while constructing the Carrier logging road. Exploration by Equity Silver from 1990 to 1992 consisted of local trenching, a small IP survey and several short diamond drill holes. Little of the work was recorded and the information available to the writer is sketchy. In 2002 Tenajon Resource completed at least one trench but do not appear to have conducted diamond drilling.

## **GEOLOGY**

The area is underlain by a succession of volcanic and sedimentary rocks ranging in age from lower Jurassic to upper Cretaceous. Andesitic to rhyolitic volcanics of the Hazelton and Kasalka Groups are dominant. Intrusive units consist of Late Cretaceous granodioritic and quartz-monzonitic stocks and minor dykes or sills related to volcanism.

Hazelton volcani-clastics composed of hematitic tuffs and ash of mainly andesitic composition underlie and host known mineralization on the prospect. Details of stratigraphy and structure are obscured by moderately deep till cover within a broad east-west trending fault controlled valley. There are indications that cross-faulting and possibly local intrusive activity have strongly influenced mineralizing events.

## **PROGRAM OBJECTIVES AND EXECUTION**

The December 2007 drilling program was designed to test for extension to mineralization at greater depth than had been done by earlier workers and to establish potential for structurally controlled mineralization south of the Carrier road. Additionally, this work sought to examine the possibility of stratigraphically controlled strata-form or strata-bound mineralization. This was achieved with a four hole program shown in Figure 3 (Appendix 1). The program was completed under contract to MoreCore Drilling Ltd. The NQ-2 core recovered is temporarily stored in Houston BC.

Drill supervision and core-logging was completed by Mr. Mark Ralph (technician) under the supervision of Andre J. Audet P.Eng.

Core was logged in detail and a large portion was split by diamond saw, sampled and submitted to Acme Laboratories for multi-element analysis. Analytical results and drill logs are provided in Appendices 2.

## **STATEMENT OF COSTS**

Costs incurred in completing this program are summarized as follows:

## **MINERALIZATION**

Economic interest centers on lapilli tuffs and related graphitic argillites forming a poorly understood stratigraphic complex that has been strongly influenced by cross faulting. Mineralization is associated in part with shear controlled 'bleached' alteration accompanied by weak to negligible quartz and carbonate stringer emplacement. These zones contain small amounts of disseminated pyrite with a fine dark grey mineral assumed to be a member of the tetrahedrite series.

**Cadillac Mining Corporation Inc.**

**Table 2**

**Silver Streak Exploration Project; December 2007**

**Statement of Costs**

Exploration Work typ Comment		Days			Totals
<b>Personnel (Name)* / F Field Days (list actual days)</b>		<b>Days/hours</b>	<b>Rate</b>	<b>Subtotal*</b>	
M Ralph/ geologist	115 hours between Dec 1 and 22	115.00	\$65.00	\$7,475.00	
contracted labour	Core splitting	145.00	\$27.50	\$3,987.50	
		sub total		\$11,462.50	
	Allocating 60% to Silver Streak			\$6,877.50	
A Audet/ geologist	9.01 days between Dec 1 and 22	9.01	\$600.00	\$5,406.00	
				\$12,283.50	<b>\$12,283.50</b>
<b>Drilling</b>		<b>No.</b>	<b>Rate</b>	<b>Subtotal</b>	
Diamond	No. of Holes, Size of Core and Metres 4 holes; AQ; 549meters	549.00	\$206.00	\$113,049.12	<b>\$113,049.12</b>
<b>Transportation</b>		<b>No.</b>	<b>Rate</b>	<b>Subtotal</b>	
Mark RalphTruck	days	11.50	\$100.00	\$1,150.00	
Ralph km rate	km	1134.00	\$0.35	\$396.90	
Cadillac leased truck	9 days at \$100	9.00	\$100.00	\$900.00	
Fuel	travel on site; costs prorata	1.00	\$550.00	\$550.00	
Other					
				\$2,996.90	<b>\$2,996.90</b>
<b>Accommodation &amp; Food</b>					
Hotel and Accomodatic	Ralph Dec 1 to 22/08		\$0.00	\$1,230.92	
amounts prorated acro	Audet Dec 1 -22; 10 days			\$1,800.00	
All charges related to	Smithers and Houston				
				\$3,030.92	<b>\$3,030.92</b>
<b>Miscellaneous</b>					
Core shack setup			\$0.00	\$1,234.50	
Other (Specify)					
				\$1,234.50	<b>\$1,234.50</b>
<b>Equipment Rentals</b>					
misc supplies and materias				\$500.00	
				\$500.00	<b>\$500.00</b>
<b>Freight, rock samples</b>					
Assaying with Acme Labs			\$0.00	\$7,000.00	
				\$7,000.00	<b>\$7,000.00</b>
<b>TAL Expenditures</b>					<b>\$140,094.94</b>

A. J. Audet P.Eng






## RESULTS AND DISCUSSION

The only mineralization of consequence encountered was seen in DDH 07-2. This hole was lost in faulted ground at a depth of 44.8m, however, the lower 28.4m, which consisted of weakly mineralized graphitic argillite, show elevated silver values averaging 28.2 ppm Ag. Drill holes DDH 07-1, 3&4 produced only short intervals carrying anomalous but subeconomic metal values. Drill logs and tables of analytical results are contained in Appendix 2. A table of drill hole locations and selected results is given below.

**Table 3 Selected Analytical Results**

Location data in UTM; Nad83 Zone 9

From (m)	To (m)	Interval (m)	Ag (g/t)
<b>DDH SS07-1</b> E645407 N6007202; Direction 110; Dip -50; TD 237.44m			
46.0	50.5	4.5	9.0
70.1	70.7	0.6	4.4
127.2	127.8	0.6	3.3
153.1	154.3	1.2	11.0
<b>DDH SS07- 2</b> E645442 N6007170; Direction 110; Dip -50; TD 44.81m			
16.4	44.8	28.4	28.2
<b>DDH SS07- 3</b> E645511 N6007029; Direction 290; Dip -50; TD 160.94m			
Anomalous Lead, Zinc and Silver			
<b>DDH SS07- 4</b> E645511 N6007029; Direction 290; Dip -70; TD 106.07m			
34.7	48.2	13.5	4.9

## CONCLUSIONS AND RECOMMENDATIONS

- Silver mineralization at the Silver Streak prospect is associated with a fine disseminated grey mineral resembling tetrahedrite.
- Controls to mineralization appear to be both structural and stratigraphic.
- Work to date suggests that the environment favouring economic grades of mineralization does not extend southward along the anticipate strike of mineralization and does not extend to depth below know surface expression.


No further work appears warranted on this target.

**Appendix 1**

**Geological Map Showing 2007 Drilling Results**

**And**

**Available Results of Historical Work**



**Appendix 2**

**Diamond Drill Logs**

**And**

**Compiled Analytical Data**

**In Pocket as Excel Files**

**DDH-SS07-01 - Final.xls**

**DDH-SS07-02 - Final.xls**

**DDH-SS07-03 - Final.xls**

**DDH-SS07-04 - Final.xls**

Interval (m)		Rock Type	Geological Description	Interval (ft)		Assay Data - Weighted Averages					
				From	To	Samp #	From	To	Int (m)	Cu-ppm	Ag-ppm
0.00	3.05	Casing		0.00	10.00						
3.05	36.76	Andesitic Flow	Green with a light pink hue dh, fgr equigranular with localized chlorite and epidote filled fractures and breccia zones. Weakly mottled dh in localized sections. Generally pervasively epidote, chlorite and silica altered with lesser magnetite as fine diss grains. Limonite coatings on fracture planes is rare and generally not apparent after 12m dh. Weak, pink pasty coating (hem + kaolinite?) down to 30m. Pervasive carbonate becomes apparent at 12m and increases to mod pervasive by 15m and continues to be moderate towards the lower contact. No sulphides were observed until the bottom 2m of this unit. Chlorite +/- epidote fractures and/or plating is common down to 28m. Dh from here high angle fractures display a dark speckled mineral which often displays a radiating acicular habit, and red specks of hem (cuprite?) - these fracture surfaces are generally dark. Also dh from 28m carbonate veinlets appear as a weak stockwork. The last 1m of this unit is bleached, sugary textured and contains up to 1% disseminated sulphides - Tetrahedrite, Galena, Pyrite in variable amounts - and possibly associated with localized carbonate veining.	10.00	120.57						
36.76	50.50	Graphitic Seds	Jet black, aphanitic with specks of calcite, calcite veinlets and dis localized hem. Abundant graphite which is polished on some slips. This may have been called phyllic seds by prev workers. Hairline veinlets of calcite is common and locally forms a breccia texture, however this is never strong enough to be a true breccia. A weak apparent remnant bedding (70 dTCA) commonly forms fracture planes. Mineralization has also been noted along these planes(?) and appears to be a dirty looking subeuhedral py (or perhaps po) (2%). Another rare very fine grained black dis submetallic sulphide was observed, however it was too small to determine its exact nature tetrahedrite (?) (<0.1%). Determination as to the quantity of this sulphide was difficult due the dark nature of both the groundmass and the sulphide. Another rare, very fine grained, steel grey, subconchoidal fractured with a rough fracture surface, brownish red streak, sulphide is likely tetrahedrite but again too small to determine with certainty (0.1%). Lower contact is a fault (65 dTCA).	120.57	165.64						
50.50	91.32	Andesitic Flow	Maroon, aphanitic-porphyrtytic (primary volc textures largely preserved?) with several bleached and/or hematized sections. Weak localized foliation. Carb veining is common but decreasing dh and locally exhibits a common green pyrophyllite (talc?) in disrupted, low angle planes.	165.64	299.53						

Interval (m)		Rock Type	Geological Description	Interval (ft)		Assay Data - Weighted Averages				
From	To			From	To	Samp #	From	To	Int (m)	Cu-ppm
91.32	97.86	Andesitic Flow	Brownish green to blue grey dh, very friable, intensely clay altered. Sharp drop in veining and where veining present it's broken and discontinuous. Mineralization in the form of wisps of tetrahedrite is difficult to asses due to the abundance of clay but may sit above 0.5% or higher in the blue grey sections. Appears to have been an agglomerate. Large localized clasts with spherulitic textures are rare.	299.53	320.98					
97.86	126.93	Andesitic Flow	Brownish green with pink - blue undertones, aphanitic-porphyritic with polymictic phenocrysts (hem altered plag, ep altered quartz?). Phenocrysts comprise 30-40% of core. Locally crushed. Veining is significantly lower and less disrupted then previous sections. Alteration is weaker then previous sections and alteration fronts are more likley to be subtle and gradational. Minor mineralization may exist, however none was observed.	320.98	416.33					
126.93	130.00	Mylonite	Intensely sheared and foliated and likely of andesitic composition. All primary texture destroyed or modified beyond recognition. Veining limited to fine hairs following foliation or as broken discontinuous chunks. Mineralization appears limited to specular hematite with Ocher hematite and possible py. Locally, a black submetallic mineral is suspect for tetrahedrite but is most likely spec hem.	416.33	426.40					
130.00	144.10	Agglomerate	Green polymictic agglomerate. Clast supported with clasts ranging from sub mm to several cm across. Generally angular to sub angular. Matrix comprises 5% of the core and host considerable carbonate, silica and chlorite/sericite. Very fine black needles can be seen in some locations. Rare trace silver white vvfgr dis AsPy(?). Other Sx may be present but they remain difficult to ascertain due to very fine xtal sizes and low abundance.	426.40	472.65					
144.10	153.33	Andesitic Flow	Purple with a localized grey bleaching, locally mottled. Moderate foliation in isolated sections. Abundant very fine grained black stubby needles are common within the groundmass (up to 2% locally). Blebs of spec hem +/- ocher hem. Rare dis very very fgr black Sx of unknown affinity. Evidence of hairline faults are common. Unusual, fleshy looking foliation controlled alteration from 149.34 to 149.60m. Localized carb filled with soft green core breccias may be flow boundaries.	472.65	502.92					
153.33	154.66	Andesitic Flow	Light pink grading to green, aphanitic-porphyritic and intensely altered. Phenocrysts are mineralized with bornite, cpy, and possibly sphalerite. Minor veinlets are very rich in Sx. Sharp alteration fronts oriented at 45 dTCA at uh and dh contacts. Possible dyke.	502.92	507.28					
154.66	237.44	Andesitic Flow	Maroon, aphanitic-porphyritic (primary volc textures largely preserved?) with several bleached and/or hematized sections and a weak localized foliation. Carb veining is common and decreasing dh and locally exhibits a green pyrophyllite in low angle disrupted veins to 177.5m after which time carb + pyrophyllite veinir gives way to carb + bright green epidote veining with chlorite/hematite inclusions. All appear unmineralized. Unit color changes to green and brownish green down hole. Green patchy epidote alteration becomes increasingly common dh past 218m. Bleached sections become more common dh, but none of these sections very strong. Overall this unit is very consistent and barren with the exception of minor changes in alteration and veining.	507.28	778.80					
237.44	237.44	EOH		778.80	778.80					

**Veining**

Key - carb=carbonate calc=calcite chl=chlorite ep=epidote pyro=pyrophyllite

From (m)	To (m)	ATCA	Type	Width (cm)	Intensity (veins per m)	Alteration Envelopes	Comments
12.00	30.40	10	carb-chl-ep	1 to 2	1.00	1mm chlorite common	Planar with localized 'blowouts' with breccia textures. Generally green with dark chloritic patches and seams. The veins appear barren. (could these be pillow selvages?)
28.90	36.76	50	calc-quartz	0.1 to 0.5			Planar with minor light green chlorite. Barren?
28.90	36.76	variable	calc-quartz	0.1 or less	30.00	<0.1cm bleaching	Erratic undulating hairlines with minor chlorite and quartz.
30.40	36.76	30	carb-chl	0.5	0.50	1mm chlorite common	Wavy discontinuous chlorite seams within a carbonate vein +/- quartz. Generally planar with erratic offshoots. Barren.
36.76	55.10	30 to 55	calc-quartz	0.01 to 0.5	>20	none	Erratic undulating hairlines to minor veinlets with a general orientation of 45 dTCA. Locally forms a weak stockwork. Dominated by carb. Rarely mineralized. Locally contains hem wisps and clasts. Cuts opalized quartz veins.
50.50	54.40	variable	opalization	0.1 to 0.5	2.00	none	Undulating light translucent blue - 6 on mohs. Barren. Cut by carb-quartz
55.10	109.72	30 to 55	calc-quartz	0.1 to 0.4	20.00	<0.1mm chlorite/sericite	Erratic undulating hairlines to minor veinlets with a general orientation of 45 dTCA. Dominated by carb. Rarely mineralized. Locally contains hem wisps and clasts and/or trace chlorite. Locally forms the matrix within breccias.
109.72	126.00	30 to 55	calc-quartz	0.1 to 0.5	12.00	<0.1mm chlorite/sericite	Weakly erratic but generally planar hairlines to minor veinlets with a general orientation of 45 dTCA. Dominated by carb. Rarely mineralized. Locally contains hem wisps and clasts and/or trace chlorite. Rarely forms the matrix within breccias.
126.00	130.00	variable	calc-quartz	0.1 to 0.2	20.00	none	Highly erratic undulating and disrupted hairlines many of which follow schistosity.
130.00	144.10	variable	calc-quartz	0.1 to 0.2	3.00	none	Highly erratic undulating and disrupted hairlines many of which are truncated.
154.66	237.44	15	pyro-calc	0.2 to 0.5	1.00		Narrow disrupted carb-pyrophyllite veins
154.66	237.44	45	calc-quartz-ep	1 to 2	0.50		Planar with carb quartz +/- epidote

## Alteration

From (m)	To (m)	Type	Intensity	Nature	Comments
3.05	36.76	silica	weak	pervasive	
3.05	36.76	epidote	weak	pervasive	
3.05	36.76	chlorite	weak	pervasive	
12.00	36.76	carbonate	mod	pervasive	
3.05	36.76	hematite	trace	pervasive	
3.05	36.76	mag	trace	pervasive	
36.76	54.40	graphite	strong	pervasive	intense near core of unit
50.50	54.40	sericite	strong	pervasive	
50.50	54.40	chlorite	weak	pervasive	
50.50	54.40	fuchsite	trace	selectively pervasive	isolated apple green translucent grains 1 to 4mm. Fuchsite??????
50.50	54.40	hematite	weak	spotty	localized to vein margins and as spots within slips
50.50	54.40	carbonate	mod	pervasive	
54.40	63.74	sericite	mod	pervasive	
54.40	63.74	chlorite	weak	pervasive	
54.40	63.74	hematite	weak	pervasive	
54.40	63.74	carbonate	weak	spotty	
62.40	63.74	biotite	weak	pervasive	brownish coloration
63.74	70.10	hematite	mod	pervasive	
63.74	70.10	carbonate	weak	pervasive	
63.74	70.10	chlorite	trace	pervasive	
70.10	92.60	sericite	weak	pervasive	locally moderate
70.10	92.60	chlorite	weak	pervasive	locally moderate
70.10	92.60	hematite	weak	pervasive	
70.10	92.60	carbonate	weak	pervasive	
78.25	92.60	silica	weak	spotty	narrow darker harder sections
92.60	97.86	chlorite	strong	pervasive	
92.60	97.86	hematite	mod	pervasive	



**Alteration - continued**

From (m)	To (m)	Type	Intensity	Nature	Comments
92.60	97.86	carbonate	weak	spotty	
92.60	97.86	biotite	weak	spotty	
97.86	125.17	biotite	weak	spotty	
97.86	125.17	hematite	mod	spotty	
97.86	125.17	chlorite	weak	spotty	localy intense from 110.15 to 114.15
97.86	125.17	epidote	trace	slectivley spotty	
97.86	125.17	carbonate	rare	spotty	
110.15	114.15	chlorite	intense	pervasive	

## Structure


















From (m)	To (m)	ATCA	Type	Comments
3.05	28.00		broken core	locally intense with a common light greenish coating. No faults observed.
50.50	51.25	45	fault	intense cataclastite with abundant white mica
62.60	62.70		fault	
66.74	68.35	50	fault	several gouge filled cataclastites. Upper 30cm intensely faulted.
70.40	70.65		breccia	localized within bleached section. Minor diss tetra. Mod dis euhedral py +/- cpy within carbonate matrix.
74.25	74.25	45	foliation	possible remnant bedding
92.40	97.86		crush breccia	intense clay alteration and crushing
110.15	114.15		crush breccia	intense clay alteration and crushing
87.00	87.00	60	foliation	trace alignment and stretching of pheno
118.00	118.00	60	foliation	trace alignment and stretching of pheno
122.00	122.00	50	foliation	trace alignment and stretching of pheno
126.20	127.10		crush breccia	weakly developed
127.10	130.00	45	shear zone	locally mylonitic, with minor chlorite schist and sericite schist. Locally crushed and frissle.
130.00	131.30		crush breccia	weakly developed

**Mineralization**

Key - tetra=tetrahedrite py=pyrite po=pyrrhotite cpy=chalcopyrite vfgr=very fine grained vvfgr=only visible with the aid of a microscope

From (m)	To (m)	%	Type	Comments
35.00	36.76	0.2	galena	disseminated grains within carb veinlets and host(?)
35.00	36.76	0.2	tetra	disseminated grains within carb veinlets and host(?)
35.00	36.76	0.2	py	disseminated grains within carb veinlets and host(?)
36.76	50.50	2	py/po	disseminated rounded grains defining foliation
36.76	50.50	0.1	tetra	vvfgr possible tetrahedrite disseminated throughout
36.76	50.50	0.1	unknown	steel grey, rough fracture surface, brownish red streak vvfgr
50.5	54.4	0.1	galena	vvfgr disseminated grains
50.5	54.4	0.5	tetra	vvfgr disseminated grains
50.4	54.4	0.1	cpy	vvfgr disseminated grains
50.4	54.4	0.1	sphalerite	vvfgr red streaks
54.40	91.32	0.3	tetra	localized within bleached sections (see alteration) as vvfgr disseminated grains and rarely with veins.
54.40	91.32	0.1	galena	localized within bleached sections (see alteration) as vvfgr disseminated grains and rarely with veins.
54.40	91.32	0.01	cpy	rare disseminated cpy within intensely bleached sections.





**Thinsection-Wholerock Samples**

Sample #	From (m)	To (m)	Interval (m)	Target	Assays
774951	47.65	47.77	0.12	Crystal Tuff - Litho	
774952	129.75	129.88	0.13	Lithic Lapilli Tuff - Litho	
774953	152.24	152.39	0.15	Crystal Tuff - Litho	

Interval (m)		Rock Type	Geological Description	Interval (ft)		Assay Data - Weighted Averages					
From	To			From	To	Samp #	From	To	Int (m)	Cu-ppm	Ag-ppm
0.00	4.57	Collar		0.00	14.99						
4.57	8.23	Polymictic Till	Mixed crystal tuff/ash tuff/mud. Most likely several boulders sitting near the surface with mud, clay, rounded pebbles and rock fragments. Appears to collar into a hematite altered ash tuff, with moderate disseminated grains of magnetite. Minor veinlets of hematite + silica. Significant core loss (>70%). No mineralization observed.	14.99	26.99						
8.23	8.93	Dyke	Pale green to greenish tan aphanitic-porphyrtytic with phenocrysts of sulphide and fine veinlets of quartz +/- sulphide (tetra, cpy, galena (?) and possible sphalerite). Appears similar to the possible dyke logged in hole 1. Upper contact not apparent (due to surface outcropping?) lower contact undulating but sharp.	26.99	29.29						
8.93	23.67	Andesitic Ash/Crystal Tuff	Interbedded ash tuff with crystal ash tuff layers. Crystal rich layers contain up to 50% subrounded white clay altered crystals in a light green matrix. Some fining of crystals is apparent as bands. Crystal layers range from 1cm to several meters and contain variable disseminated sulphides which never exceeds 0.5%. Ash layers are darker, less common, and contain fine clay altered subrounded crystals and minor disseminated sulphides. Minor soft sediment deformation such as flames, small drop stones and minor bedding offset by small slips is common. Commonly cut by erratic contorted Fe-carb veins and veinlets which can, at times, contain Sx (dark grey, sectile).	29.29	77.64						
23.67	43.30	Graphitic Seds	Dark grey to black, aphanitic, locally abundant graphite. This may be more of a phylitic sed than a graphitic sed. Intense erratic hairlines of Fe Carb cut the entire unit. Locally these Fe carb veins are broken and undulating and generally sit at a very low angle TCA.. Minor localized breccia (26.40 to 26.50). Large dis spotty xtals of py(?) generally never exceeding 1%. The bottom of this unit opened into a cave at which time the hole was terminated.	77.64	142.02						
43.30	44.81	Sand	Fine black sand likely from the hole caving and then being ground. Most of this material appears to be clay rich with abundant graphite. Abundant rounded pebbles of the upper unit were noted.	142.02	146.98						
44.81	44.81	EOH	Terminated due to cave	146.98	146.98						

**Veining**

From (m)	To (m)	ATCA	Type	Width (cm)	Intensity (veins per m)	Alteration Envelopes	Comments
----------	--------	------	------	------------	-------------------------	----------------------	----------



**Alteration**

From (m)	To (m)	Type	Intensity	Nature	Comments
----------	--------	------	-----------	--------	----------

**Mineralization**

From (m)	To (m)	%	Type	Comments
----------	--------	---	------	----------

**Structure**

From (m)	To (m)	ATCA	Type	Comments
----------	--------	------	------	----------



Sample #	From (m)	To (m)	Interval (m)	Target	Assays

Interval (m)		Rock Type	Geological Description	Interval (ft)		Assay Data - Weighted Averages					
From	To			From	To	Sample #	From	To	Int (m)	Cu-	Ag-ppb
Cadillac Mining Santa Maria 2007			<b>Hole DDH-SS07-03</b> <b>Easting: 645511 Northing: 6007029 Elevation: 819m UTM Zone 9U Nad 83</b> <b>Azimuth: 290 deg Dip: -50.0 deg Length: 160.94m/527.8ft</b> <b>Start: Dec 14 2007 Finish: Dec 15 2007</b> <b>Core Size: BQ thin wall</b> <b>Logged By: Mark Ralph</b>		<b>Other Notes</b> No Down hole survey data was gathered Collar Azimuths are true and set to 21 deg E of magnetic.						
0.00	22.34	Casing - Till	Reddish grey mud with pebbles and large clasts of overburden consisting largely of volcanoclastic rocks observed in core. Possible minor chalcocite.	0.00	73.28						
22.34	38.80	Graphitic Seds	Likely argillite with significant graphite especially near uh margin on slips. Localized vuggy quartz carb filled bx with dis silver octahedral (?) Sx and dis sphalerite. Minor veinlets. Localized grey sandy sections ranging from 1 cm to 15 cm. Generally broken. One localized gouge zone 28.9m (75 to 45 dTCA). Grey very very fine grained disseminated sulphides increasing to 5% near dh contact. Dh contact is at 45 dTCA. Localized py blebs aligned with foliation.	73.28	127.26						
38.80	47.71	Greywacke/Crystal Tuff	Grey with a hint of pink. Poorly sorted with angular chlorite replaced blades/chips, green soft rounded to subrounded grains, minor quartz. Matrix supported with clasts >1mm consisting of ~5% of core. Very very fine grained dis Sx up to 2% locally. Sx appears concentrated within darker wisps. Also, rounded 2-4mm clasts (?) of what appears to be py but may be another Sx - especially dh from 42.06m.	127.26	156.49						
47.71	52.15	Seds	Grey to tan to beige, interbedded mudstone/sandstone/pebble conglomerate. Local rip up breccia between some bedds including a mud flake breccia between a muddy and a silty layer. Other soft sed features include drop stones, sand volcanoes and flame structures. Locally convoluted and offset in what appear to be slump features. Cross cutting carb veinlets often contain minor sulphides. Total sulphides are less than 0.1% and as very very fine grains. Bedding is at 60 decreasing to 30 dTCA dh.	156.49	171.05						
52.15	55.34	Greywacke/Volc seds	Similar to unit described above except darker, coarser fragments, less sulphide and no large rounded py clasts. Sx < 1%.	171.05	181.52						
55.34	61.20	Andesite Tuff	Brown to blue grey with minor quartz carb veining. Generally fine grained with large relatively hard black rounded phenocrysts, which at time are internally cut by thin sx rich veins. Localized clasts of Sx (py +/- other sx) up to 2cm are often cut by a fine black and white checkered like bx (black material is Tetra?). Very fine diss Sx up to 3% and primarily py +/- tetra. Over all Sx < 5%. Bedding at 50 dTCA. Sharp upper contact at 70 dTCA(?). Lower contact between this and underlying sandstones shows slivers of grey wacke and other seds and sits at a low angle TCA.	181.52	200.74						
61.20	62.35	Mixed Seds	Faulted chunks of greywacke, andesite tuff, and sandstone from units described in this log. Sandstone sliver shows ooids described in previous hole as spots and tubes. Lower contact is a strong crushed breccia at 25 dTCA.	200.74	204.51						
62.35	78.98	Sandstone	Light green to beige becoming greener dh, well rounded sand sized generally greenish grains with dark flakes and grains which commonly form patches. Polymictic with a significant number of small tetra + carb bx grains similar to those described uh. Also diss tetra. Both are difficult to assess quantity due to other dark grains. Fining upwards in drill core. Strong rxn to HCL from UC to 68.5m. Crushed from 65.87m to 67.05 then chlorite schistose from 67.05 to 67.37m. Also weak spotty crushed bx from 67.37 to lower contact. Pours and poorly consolidated. Lower contact is sharp at 60. Lower 8m of unit is interbedded with agglomerate and commonly shows large rounded boulders up to 10cm across in a sandy matrix. . An aphanitic pale pink tan clast appears similar to similar to dykes seen in holes 1 and 2 and 4. bright green translucent phenos in dike (pyrophyllitic?). Also, bright green localized coloration is likely due to sericite or pyrophyllite alteration. Rare veinlets are mineralized with tetra and other sx up to 0.2% in total. Overall Sx < 5% and consists of Tetra, py, thin discontinuous seams of dis sphalerite. No galena was observed.	204.51	259.05						
78.98	160.94	Andesite Tuff/Aglomerate	Fine grained aphanitic-porphyrtyc purple andesitic tuff mixed with purple agglomerate and narrow aphanitic pink to greenish tan dykes. Locally crushed and sheared with common narrow breccia. Disrupted veinlets of fe carb +/- quartz are commonly mineralized with very very fine grained dis tetrahedrite (<0.5 in vein) and other Sx. Veins are intensely disrupted broken and convoluted through out section. Dis very very fine grained crystals and localized clusters of Sx consisting of tetra, and py are common but never in any abundance (?) (<0.5%). Clast in agglomerates commonly show volcanic textures such as spherulites and liphasea. Remnant bedding is aparent in some locations, however this may be an alteration feature aligned with foliation (65 dTCA). in some locations spherulites are flattened along foliation/bedding planes 65 dTCA. In some locations a psuedo breccia texture is apparent. Minor localized bleaching is common. Overall a wide variety of textures which can change dramatically over very short intervals makes this a complex section.	259.05	527.88						
160.94	160.94	<b>EOH</b>		527.88	527.88						

**Veining**

From (m)	To (m)	ATCA	Type	Width (cm)	Intensity (veins per m)	Alteration Envelopes	Comments
----------	--------	------	------	------------	-------------------------	----------------------	----------

Comments



**Alteration**

From (m)	To (m)	Type	Intensity	Nature	Comments
----------	--------	------	-----------	--------	----------

**Mineralization**

From (m)	To (m)	%	Type	Comments
----------	--------	---	------	----------

**Structure**

From (m)	To (m)	ATCA	Type	Comments
----------	--------	------	------	----------



**Thinsection-Wholerock Sample Key**

Sample #	From (m)	To (m)	Interval (m)	Target	Assays
774975	56.53	56.63	0.10		
774976	98.50	98.62	0.12		
774977	103.02	103.18	0.16		
774978	105.74	105.87	0.13		
774979	107.74	107.86	0.12		
774980	113.69	113.86	0.17		
774981	130.45	130.61	0.16		
774982	78.18	78.35	0.17		
774983	141.79	141.97	0.18		
774984	158.40	158.51	0.11		

Interval (m)		Rock Type	Geological Description	Interval (ft)		Assay Data - Weighted Averages						
				From	To	Samp #	From	To	Int (m)	Cu-ppm	Ag-ppm	
Cadillac Mining Silver Streak 2007			<b>Hole DDH-SS07-04</b> <b>Easting: 645511 Northing: 6007029 Elevation: 819m UTM Zone 9U Nad83</b> <b>Azimuth: 290 deg Dip: -70.0 deg Length: 106.07m/347.9ft</b> <b>Start: Dec 15 2007 Finish: Dec 16 2007</b> <b>Core Size: BQ thin wall</b> <b>Logged By: Mark Ralph</b>		<b>Other Notes</b> No Down hole survey data was gathered Collar locations are in NAD83 Collar Azimuths are true and set to 21 deg E of mag North							
0.00	17.68	Till	Reddish grey mud with pebbles and large clasts of overburden consisting largely of volcanoclastic rocks observed in core. Possible minor chalcocite. Drillers block after 17.68 reads 'wash out'.	0.00	57.99							
17.68	30.08	Graphitic Seds	Likely argillite with significant graphite especially near uh margin on slips. Localized vuggy quartz carb filled bx with disseminated silver octahedral (?) sulphide and disseminated sphalerite. Minor veinlets. Localized grey sandy sections ranging from 1 cm to 15 cm and (60dTCA). Generally broken. One localized gouge zone 28.5m (25 dTCA). Increasing grey very very fine grained disseminated sulphides increasing to 5% near dh contact. Dh contact is with a sandy layer (60dTCA).	57.99	98.66							
30.08	34.67	Greywacke/Crystal Tuff	Grey with a hint of pink. Poorly sorted with angular chlorite replaced blades/chips, green soft rounded to subrounded grains, and minor quartz. Matrix supported with clasts >1mm consisting of ~5% of core. Very very fine grained disseminated sulphides up to 2% locally.	98.66	113.72							
34.67	39.01	Seds	Grey to tan to beige, interbedded mudstone/sandstone/pebble conglomerate. Locally rip up breccia between some beds including a mud flake breccia between a muddy and a silty layer. Mud flakes are near the dh contact within the silt and above the mud suggesting right way up in the drill hole. Other soft sed features include drop stones, sand volcanoes and sandy flames. Locally convoluted and offset in what appear to be slump features. cross cutting carb veinlets often contain minor sulphides. Total sulphides are < 1% and as very very fine grains. Bedding is at 65-70 dTCA.	113.72	127.95							
39.01	50.40	Andesite Tuff	Brown to blue grey with minor quartz carb veining. Generally fine grained with large relatively hard black rounded phenocrysts. Rarely sheared and brecciated. Very fine disseminated sulphide up to 3% and primarily py. Bedding at 60dTCA. Convoluted upper contact at 75dTCA (?). Lower contact somewhat gradational at 30dTCA.	127.95	165.31							
50.40	57.83	Limestone	Light green to beige with well rounded, sand sized and generally greenish grains with dark flakes. Fining upwards in drill core. Upper 10cm shows clusters of tubes and corresponding spots (fossil?). Strong reaction to HCL throughout. Crushed from 52m to 52.92 then schistose from 52.92 to 53.30m. Also crushed and sheared from 54.20 to 54.65m. Lower contact is a fault at 55 dTCA. An aphanitic pale pink tan dike with upper contact at 60 dTCA and lower contact at 25 dTCA is similar to dykes seen in holes 1 and 2. bright green translucent phenocrysts in dyke. veinlets are mineralized with tetra and other sx up to 0.2% in total.	165.31	189.68							
57.83	106.07	Andesite Tuff/Aglomerate	Fine grained aphanitic-porphyrtyc purple andesitic tuff mixed with purple agglomerate and narrow aphanitic pink to greenish tan dykes or beds. Locally crushed and sheared with common narrow breccia. Disrupted veinlets of fe carb +/- quartz are commonly mineralized with very very fine grained dis tetrahedrite (<0.5 in vein) and other sulphides. Veins are intensely disrupted broken and convoluted through out section. Dis very very fine grained crystals and localized clusters of sulphide consisting of tetra, and py are common but never in any abundance (?) (<0.1%). Clasts in agglomerates commonly show volcanic textures such as spherulites and liphasea. Remnant bedding is aparent in some locations, however this may be an alteration feature aligned with foliation (65 dTCA). in some locations spherulites are flattened along foliation/bedding planes 65 dTCA. In some locations a psuedo breccia texture is apparent. Minor localized bleaching is common. Overall a wide variety of textures which can change dramatically over very short intervals makes this a complex section.	189.68	347.91							
106.07	106.07	<b>EOH</b>		347.91	347.91							

**Veining**

From (m)	To (m)	ATCA	Type	Width (cm)	Intensity (veins per m)	Alteration Envelopes	Comments
----------	--------	------	------	------------	-------------------------	----------------------	----------

**Alteration**

From (m)	To (m)	Type	Intensity	Nature	Comments
17.68	34.67	chlorite	mod	pervasive	
17.68	30.08	graphite	mod	selectively pervasive	
17.68	30.08	carb	mod	selectively spotty	
30.08	57.83	carb	mod	pervasive	
30.08	50.40	sericite	strong	selectively spotty	
30.08	34.67	hem	weak	selectively spotty	
30.08	34.67	kaolinite	mod	pervasive	
30.08	57.83				
34.67	39.01	hem	trace	selectively spotty	
34.67	39.01	chlorite	weak	selectively spotty	
39.01	50.40	chlorite	weak	pervasive	
39.01	50.40	hem	mod	pervasive	
50.40	57.83	sericite	strong	pervasive	
50.40	57.83	chlorite	weak	pervasive	
57.83	106.07	hem	mod	selectively pervasive	
57.83	106.07	sericite	mod	spotty	
57.83	106.07	carb	weak	spotty	
57.83	106.07	chlorite	trace	pervasive	
57.83	106.07	sericite	mod	selectively pervasive	



**Mineralization**

From (m)	To (m)	%	Type	Comments
----------	--------	---	------	----------

**Structure**

From (m)	To (m)	ATCA	Type	Comments
----------	--------	------	------	----------



Sample #	From (m)	To (m)	Interval (m)	Target	Assays

**Appendix 3**

**Certificates of analysis**

**In Pocket as PDF files**

**SMI08000468\_Certificate\_1**

**&**

**SMI08000470\_Certificate\_1**



ACME ANALYTICAL LABORATORIES LTD.  
852 E. Hastings St. Vancouver BC V6A 1R6 Canada  
Phone (604) 253-3158 Fax (604) 253-1716

[www.acmelab.com](http://www.acmelab.com)

**Client:** Cadillac Mining Exploration

3741 W. 36th Ave  
Vancouver BC V6N 2S3 Canada

Submitted By: Victor Erickson

Receiving Lab: Acme Analytical Laboratories (Vancouver) Ltd.

Received: December 19, 2007

Report Date: February 26, 2008

Page: 1 of 8

## CERTIFICATE OF ANALYSIS

SMI08000468.1

### CLIENT JOB INFORMATION

Project: Silver Streak  
Shipment ID:  
P.O. Number: ACME FILE: A718866  
Number of Samples: 198

### SAMPLE DISPOSAL

### SAMPLE PREPARATION AND ANALYTICAL PROCEDURES


Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	198	Crush, split and pulverize drill core to 150 mesh		
1DX	198	1:1:1 Aqua Regia digestion ICP-MS analysis	15	Completed

### ADDITIONAL COMMENTS

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Cadillac Mining Exploration  
3741 W. 36th Ave  
Vancouver BC V6N 2S3  
Canada

CC: Andre Audet



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.

**CERTIFICATE OF ANALYSIS**

**SMI08000468.1**

Method	WGHT	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15
Analyte	Wgt	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
774701	Drill Core	1.70	0.7	41.2	3.4	51	<0.1	82.2	23.8	765	4.02	1.9	0.3	<0.5	0.5	132	0.1	<0.1	<0.1	90	2.20
774702	Drill Core	1.50	0.8	30.2	2.5	45	<0.1	73.1	19.9	618	3.76	1.5	0.3	<0.5	0.9	46	<0.1	<0.1	<0.1	105	1.37
774703	Drill Core	1.60	0.6	40.7	2.9	46	<0.1	78.6	20.8	581	3.61	1.9	0.3	<0.5	0.8	85	<0.1	<0.1	<0.1	95	1.48
774704	Drill Core	1.30	0.6	50.6	3.3	52	<0.1	84.2	26.5	745	4.41	1.3	0.3	<0.5	0.7	131	<0.1	<0.1	<0.1	86	1.76
774705	Drill Core	3.20	0.3	34.9	4.3	50	<0.1	94.2	25.8	831	4.28	0.6	0.2	<0.5	0.6	60	0.1	<0.1	<0.1	105	3.11
774706	Drill Core	1.50	0.5	34.5	3.5	45	<0.1	86.7	22.4	1000	3.88	<0.5	0.2	<0.5	0.9	111	<0.1	<0.1	<0.1	85	6.11
774707	Drill Core	1.80	0.5	31.4	3.8	35	<0.1	71.9	19.5	1878	3.29	0.6	0.2	<0.5	1.0	127	0.1	0.1	<0.1	52	7.96
774708	Drill Core	0.80	5.2	47.4	26.8	99	0.1	63.6	22.4	3039	5.07	58.6	0.1	<0.5	0.8	146	0.5	6.2	<0.1	48	9.13
774709	Drill Core	1.50	1.6	31.5	6.5	50	<0.1	46.0	9.8	631	2.06	67.8	0.1	<0.5	0.9	69	0.2	1.5	<0.1	33	3.27
774710	Drill Core	1.40	2.9	31.0	14.1	112	<0.1	55.6	20.9	494	2.17	78.9	0.2	<0.5	0.8	84	0.6	1.8	0.3	22	2.30
774711	Drill Core	1.40	1.0	26.5	35.1	167	0.1	51.7	25.5	489	3.02	98.1	0.2	<0.5	1.3	97	0.8	2.2	0.2	23	1.37
774712	Drill Core	1.70	0.8	40.4	53.5	426	0.1	53.7	22.2	600	3.94	106.0	0.2	<0.5	1.9	86	2.4	3.1	0.3	27	1.34
774713	Drill Core	1.40	1.7	57.2	38.2	192	<0.1	53.7	19.2	745	4.66	107.1	0.2	<0.5	2.2	75	0.8	3.7	0.2	31	1.27
774714	Drill Core	3.50	0.7	39.0	30.8	172	0.3	56.2	18.5	602	3.74	107.9	0.2	<0.5	2.2	74	0.7	4.1	0.3	31	1.08
RRE 774714	Drill Core		0.8	39.5	32.4	178	0.3	56.9	18.9	601	3.87	107.5	0.2	<0.5	2.2	72	0.8	3.7	0.2	31	1.06
774715	Drill Core	1.60	2.0	32.7	88.8	352	1.4	42.2	18.2	473	3.82	103.7	0.2	<0.5	1.3	71	3.0	6.8	0.2	23	0.94
774716	Drill Core	2.20	8.4	47.2	850.6	1959	5.3	52.7	22.5	680	4.37	140.2	0.4	<0.5	1.1	69	15.7	12.5	0.1	27	1.45
774717	Drill Core	2.30	3.7	45.6	1902	7563	8.4	37.3	16.0	1006	3.78	91.1	0.1	<0.5	0.3	56	55.9	16.3	0.1	25	1.49
774718	Drill Core	1.40	4.7	144.5	2237	4435	17.5	66.6	26.6	1460	3.91	115.7	0.1	<0.5	0.2	55	42.6	48.7	0.1	25	1.44
774719	Drill Core	1.40	0.2	2.5	16.1	302	0.2	95.1	27.8	1594	4.75	30.8	<0.1	<0.5	0.3	139	0.8	1.9	<0.1	23	1.40
774720	Drill Core	0.50	0.1	0.9	7.1	27	<0.1	2.6	0.5	158	0.38	<0.5	0.7	<0.5	<0.1	42	0.3	0.2	<0.1	<2	22.17
774721	Drill Core	1.50	<0.1	22.5	6.9	370	0.1	115.7	32.7	2213	5.46	13.7	<0.1	<0.5	0.3	130	1.3	3.0	<0.1	44	2.95
774722	Drill Core	1.50	0.2	18.1	6.2	367	0.2	97.4	28.9	2018	4.62	13.4	<0.1	<0.5	0.5	110	1.5	1.3	<0.1	45	4.04
774723	Drill Core	1.30	0.1	9.6	6.5	299	<0.1	72.8	21.6	1850	4.34	4.3	<0.1	<0.5	0.6	139	1.7	1.2	<0.1	63	5.24
774724	Drill Core	1.70	0.2	12.9	8.0	148	<0.1	73.3	24.6	1208	4.41	2.7	0.2	<0.5	0.7	115	0.6	2.3	<0.1	82	4.49
774725	Drill Core	3.70	0.2	23.0	8.6	82	<0.1	58.3	24.6	1159	3.98	3.2	0.2	<0.5	0.5	127	0.4	3.2	<0.1	88	5.81
774726	Drill Core	0.50	0.1	11.6	5.2	52	<0.1	56.3	24.8	1330	3.26	2.5	0.1	<0.5	0.5	171	0.3	0.9	<0.1	73	6.95
774727	Drill Core	1.80	0.1	10.5	4.8	52	<0.1	59.1	24.9	1250	3.66	1.8	<0.1	<0.5	0.4	231	0.3	0.7	<0.1	53	6.85
774728	Drill Core	1.60	0.4	22.9	6.4	44	<0.1	59.8	25.9	1155	3.50	1.6	<0.1	<0.5	0.4	235	0.2	0.5	<0.1	51	7.03
774729	Drill Core	1.70	0.3	34.9	6.5	26	<0.1	62.3	24.6	1058	3.79	2.7	0.1	<0.5	0.5	351	<0.1	0.3	<0.1	63	6.71



ACME ANALYTICAL LABORATORIES LTD.  
 852 E. Hastings St. Vancouver BC V6A 1R6 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Cadillac Mining Exploration

3741 W. 36th Ave  
 Vancouver BC V6N 2S3 Canada

Project: Silver Streak

Report Date: February 26, 2008

Page: 2 of 8 Part 2

# CERTIFICATE OF ANALYSIS

SMI08000468.1

Method Analyte Unit MDL	1DX15 P % 0.001	1DX15 La ppm 1	1DX15 Cr ppm 1	1DX15 Mg % 0.01	1DX15 Ba ppm 1	1DX15 Ti % 0.001	1DX15 B ppm 1	1DX15 Al % 0.01	1DX15 Na % 0.001	1DX15 K % 0.01	1DX15 W ppm 0.1	1DX15 Hg ppm 0.01	1DX15 Sc ppm 0.1	1DX15 Ti ppm 0.1	1DX15 S % 0.05	1DX15 Ga ppm 1	1DX15 Se ppm 0.5	
774701	Drill Core	0.116	11	65	2.71	91	0.246	11	2.68	0.032	0.01	0.1	<0.01	4.4	<0.1	<0.05	10	<0.5
774702	Drill Core	0.128	11	58	2.61	35	0.186	4	1.80	0.045	0.05	<0.1	<0.01	4.1	<0.1	<0.05	8	<0.5
774703	Drill Core	0.125	12	53	2.60	47	0.200	5	2.14	0.049	0.02	<0.1	<0.01	3.1	<0.1	<0.05	9	<0.5
774704	Drill Core	0.107	9	53	3.44	36	0.171	5	2.63	0.033	<0.01	<0.1	<0.01	3.8	<0.1	<0.05	11	<0.5
774705	Drill Core	0.113	13	100	3.86	37	0.087	2	2.83	0.039	0.06	<0.1	<0.01	8.3	<0.1	<0.05	10	<0.5
774706	Drill Core	0.116	12	85	1.50	58	0.005	2	2.17	0.092	0.10	<0.1	<0.01	11.3	<0.1	<0.05	6	<0.5
774707	Drill Core	0.109	11	44	0.93	213	0.002	5	1.18	0.051	0.21	<0.1	<0.01	11.4	<0.1	<0.05	3	<0.5
774708	Drill Core	0.094	8	22	2.57	193	<0.001	3	0.60	0.021	0.11	<0.1	0.03	9.4	0.2	0.34	2	<0.5
774709	Drill Core	0.042	3	15	1.12	50	<0.001	5	0.43	0.023	0.20	<0.1	<0.01	5.9	<0.1	0.12	<1	<0.5
774710	Drill Core	0.035	2	12	0.92	56	<0.001	6	0.47	0.039	0.23	<0.1	0.02	6.4	<0.1	0.33	1	0.7
774711	Drill Core	0.047	2	10	0.71	72	<0.001	8	0.57	0.075	0.27	<0.1	0.05	8.6	<0.1	0.86	1	0.8
774712	Drill Core	0.041	1	11	0.78	68	<0.001	6	0.45	0.079	0.24	<0.1	0.09	9.5	<0.1	0.99	<1	0.6
774713	Drill Core	0.054	1	11	0.85	60	<0.001	6	0.43	0.078	0.23	<0.1	0.08	9.9	<0.1	1.21	<1	0.9
774714	Drill Core	0.040	1	9	0.72	65	<0.001	7	0.44	0.095	0.21	<0.1	0.07	10.3	<0.1	0.80	<1	0.6
RRE 774714	Drill Core	0.039	1	10	0.72	66	<0.001	6	0.48	0.093	0.24	<0.1	0.07	10.0	<0.1	0.85	1	<0.5
774715	Drill Core	0.032	1	6	0.57	80	<0.001	6	0.39	0.104	0.18	<0.1	0.15	9.4	0.1	1.36	<1	1.3
774716	Drill Core	0.029	1	7	0.67	76	<0.001	7	0.42	0.102	0.19	<0.1	0.45	9.6	0.2	2.21	<1	1.8
774717	Drill Core	0.032	<1	8	0.57	78	<0.001	5	0.32	0.087	0.16	<0.1	1.35	9.7	0.1	1.73	<1	1.2
774718	Drill Core	0.029	<1	8	0.52	101	<0.001	9	0.37	0.083	0.19	<0.1	1.06	9.6	0.3	1.74	<1	1.2
774719	Drill Core	0.019	1	28	0.66	393	<0.001	5	0.42	0.170	0.19	<0.1	0.05	22.2	<0.1	<0.05	<1	<0.5
774720	Drill Core	0.015	<1	<1	11.12	7	<0.001	<1	0.02	0.002	0.01	0.2	<0.01	0.2	<0.1	<0.05	<1	<0.5
774721	Drill Core	0.044	2	39	1.20	2087	<0.001	6	0.37	0.106	0.18	<0.1	0.07	16.8	<0.1	0.05	<1	<0.5
774722	Drill Core	0.072	2	37	1.39	1139	<0.001	6	0.41	0.085	0.20	<0.1	0.23	16.3	<0.1	0.09	<1	<0.5
774723	Drill Core	0.093	4	44	1.65	1683	<0.001	6	0.42	0.084	0.23	<0.1	0.14	18.3	<0.1	0.05	<1	<0.5
774724	Drill Core	0.072	5	94	1.60	507	0.006	7	0.43	0.086	0.25	<0.1	0.04	16.8	<0.1	<0.05	1	<0.5
774725	Drill Core	0.070	5	88	1.79	427	0.008	9	0.42	0.080	0.24	0.2	0.03	16.7	<0.1	<0.05	<1	<0.5
774726	Drill Core	0.064	5	65	2.15	1134	0.002	5	0.43	0.080	0.23	0.1	0.02	16.0	<0.1	<0.05	<1	<0.5
774727	Drill Core	0.065	5	44	1.95	2414	<0.001	5	0.44	0.099	0.23	<0.1	0.03	16.0	<0.1	0.05	<1	<0.5
774728	Drill Core	0.059	5	49	1.83	2340	0.001	6	0.57	0.108	0.23	<0.1	0.05	15.4	0.1	0.05	1	<0.5
774729	Drill Core	0.082	6	85	1.53	1420	0.006	5	0.88	0.205	0.21	0.2	0.01	17.1	0.2	0.07	2	<0.5



Client: **Cadillac Mining Exploration**

3741 W. 36th Ave  
Vancouver BC V6N 2S3 Canada

Project: Silver Streak  
Report Date: February 26, 2008

[www.acmelab.com](http://www.acmelab.com)

Page: 3 of 8 Part 1

## CERTIFICATE OF ANALYSIS

SMI08000468.1

Method	WGHT	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	
Analyte	Wgt	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
774730	Drill Core	4.50	0.4	23.7	6.7	33	<0.1	67.7	25.9	1024	3.74	2.8	0.2	<0.5	0.6	234	0.2	0.8	<0.1	75	6.18
774731	Drill Core	4.50	0.2	14.3	19.1	68	<0.1	50.6	27.6	1075	5.15	6.4	0.4	1.1	0.9	240	0.4	2.9	<0.1	48	4.46
774732	Drill Core	3.00	0.3	14.4	21.6	53	<0.1	46.0	27.0	1122	5.64	6.7	0.5	0.6	1.0	269	0.3	3.4	<0.1	73	5.22
774733	Drill Core	1.50	0.2	14.7	12.1	57	<0.1	41.5	24.7	1111	4.81	4.8	0.3	1.5	0.8	268	0.3	1.6	<0.1	51	4.98
774734	Drill Core	0.90	10.4	867.5	19.1	214	4.4	66.3	35.8	1315	3.57	312.0	<0.1	2.0	0.4	211	1.6	120.5	0.1	26	6.03
774735	Drill Core	0.90	2.6	79.5	9.8	115	0.7	84.8	40.3	1270	4.55	41.7	<0.1	<0.5	0.5	249	0.7	11.2	<0.1	46	6.31
774736	Drill Core	1.30	0.2	5.1	4.6	105	<0.1	79.9	35.7	1159	4.54	2.8	<0.1	1.2	0.5	317	0.4	0.5	<0.1	36	4.94
774737	Drill Core	1.80	0.2	8.3	7.3	82	<0.1	50.4	25.3	1019	5.04	1.8	0.2	<0.5	0.7	276	0.4	0.7	<0.1	75	5.09
774738	Drill Core	1.60	0.5	36.3	6.0	116	0.2	81.9	31.0	1008	5.02	8.7	<0.1	1.6	0.6	285	0.4	1.1	<0.1	52	4.27
774739	Drill Core	2.00	0.5	22.3	5.5	109	0.1	77.5	30.9	942	5.29	5.4	<0.1	<0.5	0.6	293	0.3	0.5	<0.1	48	3.81
774740	Drill Core	0.60	0.2	1.3	1.5	16	<0.1	2.8	0.8	224	0.44	<0.5	1.3	0.9	0.2	52	<0.1	<0.1	<0.1	<2	25.41
774741	Drill Core	1.50	2.3	65.0	11.9	104	0.7	78.8	36.8	951	5.21	26.9	0.1	1.2	0.7	242	0.2	0.9	<0.1	52	3.89
774742	Drill Core	1.60	1.3	63.2	6.1	95	0.3	63.6	33.0	1119	5.59	23.6	<0.1	1.4	0.6	304	0.1	0.5	<0.1	50	4.33
774743	Drill Core	1.60	0.5	59.7	7.0	86	0.2	76.7	30.3	1202	4.73	14.4	<0.1	0.6	0.6	386	0.2	0.6	<0.1	53	4.52
774744	Drill Core	3.00	0.5	28.7	7.5	51	<0.1	89.1	28.0	910	4.44	3.5	0.2	<0.5	0.8	333	<0.1	0.2	<0.1	99	4.30
774745	Drill Core	4.90	0.5	34.8	3.9	32	<0.1	87.5	27.8	803	4.32	2.9	0.2	0.7	0.7	222	<0.1	<0.1	<0.1	91	3.14
774746	Drill Core	5.10	0.5	21.4	5.2	35	<0.1	62.2	24.5	893	4.14	3.5	0.2	<0.5	0.6	235	<0.1	0.3	<0.1	75	3.87
RRE 774746	Drill Core		0.5	23.2	5.4	38	<0.1	75.5	28.7	959	4.56	3.6	0.2	1.7	0.7	261	<0.1	0.3	<0.1	82	4.04
774747	Drill Core	5.00	0.5	19.6	11.2	61	<0.1	60.7	25.4	1070	4.15	3.3	0.2	<0.5	0.7	204	0.1	0.7	<0.1	84	3.87
774748	Drill Core	3.50	0.4	20.7	10.5	66	<0.1	58.1	30.8	1118	3.97	2.3	0.2	<0.5	0.6	177	0.2	0.8	<0.1	82	4.24
774749	Drill Core	1.40	0.2	72.3	8.6	60	0.2	55.6	30.9	630	4.19	3.4	0.2	0.8	0.5	255	0.3	0.7	<0.1	33	3.25
774750	Drill Core	1.70	0.2	12.1	23.6	55	<0.1	43.9	24.7	778	5.33	5.0	0.3	<0.5	0.7	250	0.3	2.4	<0.1	34	2.94
774751	Drill Core	1.60	0.2	10.1	24.7	55	<0.1	46.9	27.1	1031	5.35	6.3	0.2	0.9	0.6	269	0.3	2.6	<0.1	36	4.46
774752	Drill Core	1.30	0.2	15.3	15.7	45	<0.1	33.7	19.2	765	4.49	4.0	0.2	<0.5	0.7	257	0.3	1.6	<0.1	38	3.74
774753	Drill Core	1.50	0.2	15.6	11.6	46	<0.1	35.7	18.1	522	4.27	4.8	0.2	1.1	0.7	280	0.2	1.0	<0.1	41	2.73
774754	Drill Core	4.30	0.3	11.0	13.0	75	<0.1	56.8	30.0	1195	4.15	3.2	0.2	<0.5	0.7	199	0.2	0.9	<0.1	83	4.89
774755	Drill Core	4.40	0.3	12.4	15.8	80	<0.1	54.9	28.5	1063	4.29	3.0	0.3	1.4	0.8	215	0.3	0.8	<0.1	85	4.58
774756	Drill Core	4.70	0.3	11.9	15.4	77	<0.1	53.5	27.0	909	4.13	3.8	0.2	1.0	0.8	200	0.2	0.5	<0.1	78	4.11
774757	Drill Core	0.70	0.2	147.4	12.5	83	0.7	55.0	25.9	1168	3.65	2.8	0.2	1.2	0.7	212	0.2	0.3	<0.1	68	4.00
774758	Drill Core	3.30	0.3	14.8	22.0	99	<0.1	64.9	31.7	1551	4.49	5.1	0.3	<0.5	1.0	219	0.3	0.8	<0.1	84	4.78



ACME ANALYTICAL LABORATORIES LTD.  
 852 E. Hastings St. Vancouver BC V6A 1R6 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Cadillac Mining Exploration

3741 W. 36th Ave  
 Vancouver BC V6N 2S3 Canada

Project: Silver Streak

Report Date: February 26, 2008

Page: 3 of 8 Part 2

# CERTIFICATE OF ANALYSIS

SMI08000468.1

Method Analyte Unit MDL	1DX15 P % 0.001	1DX15 La ppm 1	1DX15 Cr ppm 1	1DX15 Mg % 0.01	1DX15 Ba ppm 1	1DX15 Ti % 0.001	1DX15 B ppm 1	1DX15 Al % 0.01	1DX15 Na % 0.001	1DX15 K % 0.01	1DX15 W ppm 0.1	1DX15 Hg ppm 0.01	1DX15 Sc ppm 0.1	1DX15 Ti ppm 0.1	1DX15 S % 0.05	1DX15 Ga ppm 1	1DX15 Se ppm 0.5	
774730	Drill Core	0.077	6	69	1.99	368	0.007	6	0.93	0.163	0.18	0.1	<0.01	15.7	0.1	<0.05	2	<0.5
774731	Drill Core	0.084	6	57	1.79	464	0.032	7	0.51	0.137	0.21	0.4	<0.01	16.1	<0.1	<0.05	1	<0.5
774732	Drill Core	0.112	7	55	2.23	253	0.032	8	0.63	0.187	0.25	0.6	<0.01	17.6	<0.1	<0.05	1	<0.5
774733	Drill Core	0.088	7	39	2.04	375	0.025	9	0.46	0.169	0.21	0.4	<0.01	14.4	<0.1	<0.05	1	<0.5
774734	Drill Core	0.053	5	13	2.53	100	<0.001	5	0.38	0.116	0.18	<0.1	3.69	9.1	2.3	1.23	<1	<0.5
774735	Drill Core	0.073	5	17	2.81	455	<0.001	5	0.47	0.140	0.23	0.1	0.30	11.6	1.4	0.40	<1	<0.5
774736	Drill Core	0.066	6	20	2.35	1344	0.001	6	0.55	0.179	0.25	<0.1	0.02	14.5	0.1	<0.05	1	<0.5
774737	Drill Core	0.077	7	32	2.30	1216	0.009	6	0.47	0.159	0.23	0.2	<0.01	13.3	0.1	<0.05	<1	<0.5
774738	Drill Core	0.073	4	17	2.59	1198	<0.001	6	0.45	0.133	0.24	<0.1	0.06	11.8	0.3	0.14	<1	<0.5
774739	Drill Core	0.070	5	20	2.57	934	0.001	6	0.47	0.160	0.23	0.1	0.08	12.6	0.2	0.09	<1	<0.5
774740	Drill Core	0.027	<1	2	13.61	23	0.002	2	0.07	0.003	0.05	<0.1	<0.01	0.3	<0.1	<0.05	<1	<0.5
774741	Drill Core	0.081	5	27	2.66	212	0.001	8	0.67	0.156	0.20	0.1	0.15	11.7	2.1	0.82	2	<0.5
774742	Drill Core	0.074	5	26	3.32	203	<0.001	7	0.80	0.171	0.23	<0.1	0.04	12.8	1.1	0.34	2	<0.5
774743	Drill Core	0.063	6	39	3.16	553	<0.001	6	1.18	0.143	0.22	<0.1	0.03	12.6	0.5	0.15	3	<0.5
774744	Drill Core	0.086	8	83	2.63	292	0.010	6	1.39	0.243	0.16	0.1	<0.01	16.0	<0.1	<0.05	4	<0.5
774745	Drill Core	0.080	7	91	2.86	118	0.007	6	1.45	0.246	0.12	0.1	<0.01	14.7	<0.1	<0.05	3	<0.5
774746	Drill Core	0.084	7	59	2.53	220	0.005	6	0.99	0.208	0.19	<0.1	<0.01	14.1	<0.1	<0.05	2	<0.5
RRE 774746	Drill Core	0.086	7	67	2.80	239	0.007	7	1.07	0.216	0.21	<0.1	<0.01	15.7	<0.1	<0.05	2	<0.5
774747	Drill Core	0.088	8	56	2.32	355	0.004	6	1.06	0.269	0.19	<0.1	<0.01	14.3	<0.1	<0.05	2	<0.5
774748	Drill Core	0.090	8	48	2.31	59	0.008	5	0.87	0.220	0.21	<0.1	<0.01	14.0	<0.1	<0.05	2	<0.5
774749	Drill Core	0.182	6	33	1.66	1071	0.012	5	0.57	0.189	0.21	0.1	<0.01	15.7	<0.1	<0.05	1	<0.5
774750	Drill Core	0.057	5	49	1.45	652	0.015	5	0.51	0.221	0.20	0.2	<0.01	18.8	<0.1	<0.05	<1	<0.5
774751	Drill Core	0.042	7	46	2.04	234	0.013	5	0.50	0.227	0.20	<0.1	<0.01	18.8	<0.1	<0.05	<1	<0.5
774752	Drill Core	0.106	7	37	1.61	1107	0.015	7	0.50	0.205	0.20	0.2	<0.01	17.0	<0.1	<0.05	<1	<0.5
774753	Drill Core	0.103	5	42	1.25	1766	0.015	5	0.53	0.232	0.21	0.1	<0.01	17.2	0.1	<0.05	1	<0.5
774754	Drill Core	0.094	7	40	2.55	105	0.006	5	0.67	0.190	0.24	<0.1	<0.01	15.3	0.1	<0.05	1	<0.5
774755	Drill Core	0.092	8	43	2.79	299	0.005	5	0.62	0.232	0.26	<0.1	<0.01	16.4	0.1	<0.05	<1	<0.5
774756	Drill Core	0.091	7	40	2.90	71	0.003	6	0.65	0.244	0.27	<0.1	<0.01	15.1	0.1	<0.05	<1	0.8
774757	Drill Core	0.086	7	34	2.93	1099	0.002	6	0.63	0.220	0.22	<0.1	<0.01	14.2	0.1	<0.05	1	<0.5
774758	Drill Core	0.104	9	45	2.89	128	0.005	6	0.86	0.286	0.27	<0.1	<0.01	17.7	0.1	<0.05	1	<0.5



ACME ANALYTICAL LABORATORIES LTD.  
852 E. Hastings St. Vancouver BC V6A 1R6 Canada  
Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Cadillac Mining Exploration

3741 W. 36th Ave  
Vancouver BC V6N 2S3 Canada

Project: Silver Streak

Report Date: February 26, 2008

Page: 4 of 8 Part 1

# CERTIFICATE OF ANALYSIS

# SMI08000468.1

Method Analyte Unit MDL	WGHT	1DX15 Mo	1DX15 Cu	1DX15 Pb	1DX15 Zn	1DX15 Ag	1DX15 Ni	1DX15 Co	1DX15 Mn	1DX15 Fe	1DX15 As	1DX15 U	1DX15 Au	1DX15 Th	1DX15 Sr	1DX15 Cd	1DX15 Sb	1DX15 Bi	1DX15 V	1DX15 Ca
	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
	0.01	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01
774759 Drill Core	7.30	0.2	32.0	26.8	68	0.1	43.2	23.5	993	5.02	9.2	0.3	1.7	0.8	277	0.4	1.3	<0.1	49	3.39
774760 Drill Core	0.70	0.3	1.5	1.8	20	<0.1	3.2	0.9	278	0.50	<0.5	1.2	0.6	<0.1	70	<0.1	<0.1	<0.1	2	29.12
774761 Drill Core	1.50	0.3	68.5	46.4	57	0.1	31.0	18.3	542	5.37	17.2	0.4	<0.5	0.9	273	0.4	2.2	<0.1	38	2.61
774762 Drill Core	1.20	0.3	7.6	41.0	64	<0.1	47.8	24.3	546	5.46	13.4	0.4	1.1	0.8	254	0.2	1.9	<0.1	59	2.98
774763 Drill Core	1.10	0.4	8.6	37.5	78	<0.1	56.6	27.4	693	5.57	13.0	0.4	1.1	0.8	273	0.5	1.8	<0.1	76	3.45
774764 Drill Core	4.20	0.3	5.1	32.1	83	<0.1	64.1	31.2	1040	4.78	13.2	0.3	1.3	0.7	242	0.4	1.5	<0.1	95	4.06
774765 Drill Core	4.60	0.3	6.9	21.3	47	<0.1	56.0	27.2	872	4.47	8.2	0.3	<0.5	0.8	229	0.2	0.9	<0.1	88	4.11
774766 Drill Core	4.60	0.4	14.1	17.5	40	<0.1	54.6	27.7	932	4.25	7.1	0.3	<0.5	0.8	254	0.1	0.4	<0.1	93	4.25
774767 Drill Core	2.90	0.4	2.2	37.3	121	<0.1	59.9	31.0	1268	4.41	7.9	0.3	<0.5	0.8	194	0.6	2.3	<0.1	100	5.43
774768 Drill Core	3.20	0.3	6.9	32.2	121	<0.1	49.1	25.3	1332	4.76	8.2	0.2	<0.5	0.7	166	0.5	2.9	<0.1	65	3.93
774769 Drill Core	0.80	0.3	773.1	51.8	398	3.3	67.7	31.8	1974	4.49	18.7	0.2	1.4	0.7	162	1.9	3.7	<0.1	42	4.54
774770 Drill Core	1.50	0.3	6.6	58.8	153	<0.1	38.3	16.6	783	5.06	15.2	0.3	<0.5	1.4	150	0.6	4.8	<0.1	63	2.36
774771 Drill Core	1.00	0.3	264.5	50.2	674	1.0	85.6	30.1	1811	4.12	14.2	0.3	3.6	1.2	175	2.4	3.3	<0.1	66	3.91
774772 Drill Core	0.90	0.5	5.7	54.6	351	0.2	50.9	21.3	1073	5.47	14.6	0.5	2.5	1.4	177	1.3	4.3	<0.1	98	3.22
774773 Drill Core	1.60	0.3	3.4	33.9	145	<0.1	41.1	17.2	592	3.95	9.4	0.3	<0.5	1.5	151	0.5	2.3	<0.1	74	2.90
774774 Drill Core	2.60	0.4	5.5	30.5	166	<0.1	55.6	27.8	1068	4.36	11.0	0.3	<0.5	1.4	155	0.6	2.2	<0.1	68	4.37
774775 Drill Core	4.80	0.3	4.9	35.7	157	<0.1	43.7	25.2	1040	4.46	11.6	0.2	<0.5	1.3	178	0.5	2.0	<0.1	54	4.06
774776 Drill Core	4.90	0.3	4.7	38.1	139	<0.1	47.8	27.2	937	4.77	12.8	0.3	<0.5	1.5	159	0.6	2.1	<0.1	58	3.83
774777 Drill Core	1.70	0.3	19.0	28.4	173	<0.1	72.0	32.4	1093	4.05	11.4	0.3	<0.5	1.3	146	0.6	1.4	<0.1	41	4.58
774778 Drill Core	4.70	0.2	18.4	14.7	203	<0.1	64.0	25.6	946	3.37	4.0	0.1	<0.5	1.1	122	0.6	0.6	<0.1	66	4.58
774779 Drill Core	4.50	0.1	6.4	15.9	264	<0.1	63.8	24.2	1017	3.15	3.1	<0.1	<0.5	1.0	138	0.6	0.6	<0.1	46	4.80
774780 Drill Core	0.80	0.2	1.3	1.1	13	<0.1	1.8	0.9	190	0.41	<0.5	1.2	<0.5	0.1	39	<0.1	<0.1	<0.1	4	21.72
774781 Drill Core	2.00	0.1	7.2	13.0	197	<0.1	58.3	25.6	1055	3.46	2.9	<0.1	<0.5	0.9	143	0.4	0.4	<0.1	28	4.48
RRE 774781 Drill Core		0.1	7.8	14.2	210	<0.1	62.7	27.0	1083	3.59	3.4	<0.1	<0.5	1.0	150	0.5	0.4	<0.1	29	4.84
774782 Drill Core	3.40	0.2	6.0	20.4	289	<0.1	47.9	24.9	1038	3.78	4.1	<0.1	<0.5	1.3	151	0.9	0.5	<0.1	53	4.29
774783 Drill Core	1.50	<0.1	10.3	12.8	247	<0.1	39.9	18.9	703	3.61	2.3	<0.1	<0.5	1.2	133	0.8	0.4	<0.1	36	3.17
774784 Drill Core	0.50	0.1	20.2	11.6	354	<0.1	50.5	24.2	911	3.40	2.7	<0.1	<0.5	0.8	147	1.4	0.7	<0.1	33	5.12
774785 Drill Core	1.60	0.1	34.1	11.2	324	0.1	52.1	28.4	1318	3.93	4.4	<0.1	<0.5	0.8	162	1.1	2.1	<0.1	29	5.62
774786 Drill Core	2.40	0.2	8.6	10.6	284	<0.1	61.0	24.1	972	4.06	3.3	<0.1	<0.5	0.9	117	0.9	0.5	<0.1	44	4.93
774787 Drill Core	1.30	0.8	808.6	17.8	261	5.4	61.6	26.6	1065	2.91	11.6	<0.1	<0.5	0.9	112	1.0	55.3	<0.1	49	5.71



ACME ANALYTICAL LABORATORIES LTD.  
 852 E. Hastings St. Vancouver BC V6A 1R6 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Cadillac Mining Exploration

3741 W. 36th Ave  
 Vancouver BC V6N 2S3 Canada

Project: Silver Streak

Report Date: February 26, 2008

Page: 4 of 8 Part 2

CERTIFICATE OF ANALYSIS

SMI08000468.1

Method Analyte Unit MDL	1DX15 P % 0.001	1DX15 La ppm 1	1DX15 Cr ppm 1	1DX15 Mg % 0.01	1DX15 Ba ppm 1	1DX15 Ti % 0.001	1DX15 B ppm 1	1DX15 Al % 0.01	1DX15 Na % 0.001	1DX15 K % 0.01	1DX15 W ppm 0.1	1DX15 Hg ppm 0.01	1DX15 Sc ppm 0.1	1DX15 Ti ppm 0.1	1DX15 S % 0.05	1DX15 Ga ppm 1	1DX15 Se ppm 0.5	
774759	Drill Core	0.042	6	41	1.80	1150	0.010	6	0.59	0.286	0.24	<0.1	<0.01	16.2	0.1	<0.05	1	<0.5
774760	Drill Core	0.020	<1	1	14.52	18	0.001	1	0.05	0.003	0.03	<0.1	<0.01	0.3	<0.1	<0.05	<1	<0.5
774761	Drill Core	0.042	6	44	1.49	854	0.009	7	0.60	0.302	0.25	<0.1	<0.01	14.8	0.1	<0.05	<1	<0.5
774762	Drill Core	0.083	6	49	1.63	211	0.010	7	0.61	0.279	0.24	<0.1	<0.01	16.4	0.1	<0.05	1	<0.5
774763	Drill Core	0.089	7	49	1.92	118	0.010	7	0.72	0.283	0.28	<0.1	<0.01	15.9	0.1	<0.05	1	<0.5
774764	Drill Core	0.085	7	48	2.43	99	0.006	7	0.64	0.239	0.24	<0.1	<0.01	15.1	0.1	<0.05	1	<0.5
774765	Drill Core	0.085	7	49	2.82	64	0.005	7	0.70	0.266	0.26	<0.1	<0.01	14.1	0.1	<0.05	1	<0.5
774766	Drill Core	0.092	7	59	2.46	125	0.003	5	0.78	0.250	0.24	<0.1	<0.01	14.1	0.2	<0.05	1	<0.5
774767	Drill Core	0.098	7	52	2.08	57	0.005	6	0.81	0.211	0.27	<0.1	<0.01	15.1	0.2	<0.05	1	<0.5
774768	Drill Core	0.057	6	43	1.45	891	0.016	7	0.54	0.157	0.22	<0.1	<0.01	14.9	0.1	<0.05	1	<0.5
774769	Drill Core	0.019	5	25	1.57	1892	0.006	8	0.60	0.177	0.27	<0.1	0.17	14.4	0.2	0.06	1	<0.5
774770	Drill Core	0.070	6	31	0.80	113	0.010	7	0.64	0.192	0.28	0.1	<0.01	14.3	0.1	<0.05	1	<0.5
774771	Drill Core	0.057	6	36	1.26	1921	0.006	6	0.68	0.188	0.29	0.1	0.08	14.1	0.2	0.05	1	<0.5
774772	Drill Core	0.129	7	37	1.07	1425	0.014	9	0.84	0.184	0.34	0.6	0.02	13.0	0.2	<0.05	2	<0.5
774773	Drill Core	0.159	5	40	1.05	310	0.010	6	0.72	0.148	0.29	0.5	<0.01	11.3	0.1	<0.05	1	<0.5
774774	Drill Core	0.189	8	39	1.54	288	0.015	7	0.71	0.131	0.30	0.8	<0.01	11.4	0.2	<0.05	2	<0.5
774775	Drill Core	0.085	8	38	1.60	434	0.010	6	0.65	0.139	0.27	0.4	<0.01	11.7	0.1	<0.05	1	<0.5
774776	Drill Core	0.106	9	47	1.46	249	0.011	7	0.75	0.152	0.32	0.6	<0.01	12.0	0.1	<0.05	2	<0.5
774777	Drill Core	0.155	9	34	1.87	241	0.018	8	0.76	0.130	0.31	0.7	0.02	11.5	0.2	<0.05	2	<0.5
774778	Drill Core	0.104	7	47	2.07	386	0.017	6	0.54	0.085	0.23	0.3	0.01	10.9	0.1	<0.05	1	<0.5
774779	Drill Core	0.122	8	43	2.13	340	0.015	6	0.55	0.091	0.25	0.1	<0.01	11.1	0.1	<0.05	1	<0.5
774780	Drill Core	0.020	<1	1	12.89	13	0.002	1	0.06	0.003	0.03	<0.1	<0.01	0.3	<0.1	<0.05	<1	<0.5
774781	Drill Core	0.116	10	43	1.93	516	0.031	6	0.62	0.097	0.27	<0.1	<0.01	10.1	0.1	<0.05	2	<0.5
RRE 774781	Drill Core	0.131	11	46	2.08	502	0.032	7	0.64	0.102	0.29	0.1	<0.01	10.7	0.1	<0.05	2	<0.5
774782	Drill Core	0.151	11	38	1.67	831	0.028	8	0.77	0.116	0.34	0.1	<0.01	12.1	0.1	<0.05	2	<0.5
774783	Drill Core	0.158	10	39	1.11	1308	0.023	9	0.80	0.101	0.36	0.1	<0.01	12.9	0.2	<0.05	2	<0.5
774784	Drill Core	0.145	9	32	1.60	1025	0.005	9	0.80	0.086	0.35	<0.1	<0.01	13.4	0.2	<0.05	1	<0.5
774785	Drill Core	0.116	8	40	2.04	1891	0.007	7	0.56	0.067	0.24	0.2	<0.01	11.5	0.1	<0.05	<1	<0.5
774786	Drill Core	0.140	6	49	1.67	1464	0.006	8	0.59	0.059	0.27	0.5	<0.01	11.4	0.1	<0.05	<1	<0.5
774787	Drill Core	0.112	7	24	1.89	255	0.001	7	0.52	0.057	0.25	<0.1	0.12	10.8	0.2	<0.05	<1	<0.5



ACME ANALYTICAL LABORATORIES LTD.

852 E. Hastings St. Vancouver BC V6A 1R6 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client:

**Cadillac Mining Exploration**

3741 W. 36th Ave  
 Vancouver BC V6N 2S3 Canada

Project:

Silver Streak

Report Date:

February 26, 2008

Page:

5 of 8

Part 1

## CERTIFICATE OF ANALYSIS

SMI08000468.1

Method Analyte Unit MDL	WGHT Wgt kg 0.01	1DX15 Mo ppm 0.1	1DX15 Cu ppm 0.1	1DX15 Pb ppm 0.1	1DX15 Zn ppm 1	1DX15 Ag ppm 0.1	1DX15 Ni ppm 0.1	1DX15 Co ppm 0.1	1DX15 Mn ppm 1	1DX15 Fe % 0.01	1DX15 As ppm 0.5	1DX15 U ppm 0.1	1DX15 Au ppb 0.5	1DX15 Th ppm 0.1	1DX15 Sr ppm 1	1DX15 Cd ppm 0.1	1DX15 Sb ppm 0.1	1DX15 Bi ppm 0.1	1DX15 V ppm 2	1DX15 Ca % 0.01	
774788	Drill Core	0.40	49.6	2710	138.9	271	29.0	67.6	30.6	1250	3.62	26.3	<0.1	<0.5	0.7	140	1.3	98.0	<0.1	72	6.75
774789	Drill Core	0.50	0.2	117.3	16.6	354	0.6	77.2	31.4	1197	4.15	2.6	<0.1	<0.5	0.7	159	1.5	3.8	<0.1	97	7.00
774790	Drill Core	3.80	0.3	7.1	31.3	300	<0.1	58.5	24.7	1365	4.47	4.5	0.1	<0.5	0.9	154	0.7	1.4	<0.1	102	5.29
774791	Drill Core	1.50	0.2	15.3	57.2	318	0.2	85.2	25.1	1729	4.42	6.2	0.2	<0.5	1.1	150	0.1	1.0	<0.1	97	4.49
774792	Drill Core	1.10	0.3	58.4	57.8	230	0.7	88.8	26.1	1737	4.11	2.6	0.2	<0.5	1.0	261	0.3	0.3	<0.1	96	5.27
774793	Drill Core	2.10	0.3	16.3	66.7	130	0.2	88.5	25.3	1277	4.64	8.1	0.2	<0.5	1.1	185	2.6	0.6	<0.1	104	4.95
774794	Drill Core	4.60	0.4	38.7	19.0	183	0.1	88.9	26.3	1261	4.53	13.4	0.3	<0.5	1.0	426	1.0	0.5	<0.1	101	6.94
774795	Drill Core	5.10	0.3	51.0	30.0	173	0.1	92.8	27.0	823	4.52	5.2	0.4	<0.5	1.2	150	0.4	0.4	<0.1	115	4.38
774796	Drill Core	4.50	0.6	74.6	6.8	64	<0.1	85.5	24.2	843	4.36	12.5	0.4	<0.5	1.1	147	0.1	1.0	<0.1	149	6.00
774797	Drill Core	1.50	0.8	35.1	7.0	67	<0.1	90.5	24.8	696	4.40	5.9	0.6	<0.5	1.4	57	0.1	<0.1	<0.1	136	4.26
774798	Drill Core	5.70	0.6	5.8	2.5	66	<0.1	97.8	26.0	653	4.18	2.4	0.6	<0.5	1.3	261	<0.1	<0.1	<0.1	135	2.24
774799	Drill Core	1.00	0.3	39.0	16.2	105	0.6	48.5	21.1	1374	5.24	7.4	0.3	<0.5	2.1	117	0.4	2.2	<0.1	76	5.41
774800	Drill Core	0.80	0.3	2.3	1.9	30	<0.1	31.2	8.8	348	1.50	1.1	0.9	<0.5	0.5	164	<0.1	<0.1	<0.1	50	17.21
774801	Drill Core	3.00	0.9	47.6	124.0	398	2.4	108.2	31.6	1296	5.54	12.7	<0.1	1.4	0.5	170	2.3	7.8	<0.1	68	6.10
774802	Drill Core	1.50	1.6	52.7	278.6	440	3.0	108.4	39.2	1206	5.70	22.5	0.1	0.9	0.7	136	2.5	9.5	<0.1	67	5.13
774803	Drill Core	1.00	0.8	63.9	196.9	618	4.2	145.4	44.2	1621	6.36	7.9	0.1	0.5	0.6	146	2.2	13.0	<0.1	73	5.61
774804	Drill Core	1.30	1.0	153.3	856.2	1049	10.0	145.8	42.0	1985	7.44	21.4	<0.1	<0.5	0.5	173	6.4	61.2	<0.1	73	7.82
774805	Drill Core	1.50	2.1	200.3	1619	830	12.0	94.2	27.9	1346	5.31	30.1	<0.1	<0.5	0.6	123	6.4	62.8	<0.1	67	5.86
774806	Drill Core	1.40	5.0	129.7	1838	912	8.8	82.5	26.2	2154	6.13	28.4	0.1	1.1	0.6	140	8.2	51.3	<0.1	79	8.51
774807	Drill Core	1.30	2.1	136.9	1991	691	8.7	88.1	26.7	1810	5.63	26.5	<0.1	<0.5	0.5	144	6.9	50.8	<0.1	71	8.25
774808	Drill Core	1.60	1.9	84.8	1466	1368	5.4	87.2	23.8	1467	5.45	21.3	<0.1	<0.5	0.6	115	14.7	27.3	<0.1	74	7.28
RRE 774808	Drill Core		2.0	95.3	1448	1379	6.0	85.3	22.9	1478	5.35	22.9	<0.1	<0.5	0.7	116	14.9	32.3	<0.1	76	7.19
774809	Drill Core	1.60	2.2	327.0	1810	1192	18.6	85.8	24.0	1549	5.41	74.1	<0.1	<0.5	0.8	98	11.7	99.8	<0.1	74	5.85
774810	Drill Core	1.90	3.0	590.2	2006	1811	36.3	106.5	33.3	2121	6.79	121.2	0.1	<0.5	0.7	106	18.7	177.0	<0.1	85	6.28
774811	Drill Core	2.50	2.9	288.4	1741	638	30.4	94.4	32.7	842	3.89	199.5	0.3	<0.5	3.2	67	7.9	92.0	0.3	30	1.61
774812	Drill Core	1.30	12.8	484.2	246.9	700	35.7	87.8	35.3	2118	4.31	235.0	0.2	<0.5	1.9	82	8.5	156.3	0.2	31	4.48
774813	Drill Core	3.30	24.6	560.8	1343	1510	43.8	127.8	50.1	4783	6.72	296.5	0.2	<0.5	0.9	108	16.3	199.1	<0.1	52	6.72
774814	Drill Core	0.60	1.1	11.2	9.1	51	0.1	43.6	17.4	787	4.08	5.2	0.6	<0.5	2.4	159	0.2	1.0	<0.1	96	3.34
774815	Drill Core	4.10	10.4	946.2	4451	2011	57.2	106.5	47.1	1479	3.74	336.6	0.3	<0.5	2.4	52	26.9	285.2	0.3	31	1.66
774816	Drill Core	3.90	4.8	229.0	1443	1004	16.1	106.5	40.2	1142	4.10	213.0	0.4	<0.5	2.4	59	10.1	67.7	0.3	33	1.40



ACME ANALYTICAL LABORATORIES LTD.  
 852 E. Hastings St. Vancouver BC V6A 1R6 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Cadillac Mining Exploration

3741 W. 36th Ave  
 Vancouver BC V6N 2S3 Canada

Project: Silver Streak

Report Date: February 26, 2008

Page: 5 of 8 Part 2

# CERTIFICATE OF ANALYSIS

SMI08000468.1

Method Analyte Unit MDL	1DX15 P % 0.001	1DX15 La ppm 1	1DX15 Cr ppm 1	1DX15 Mg % 0.01	1DX15 Ba ppm 1	1DX15 Ti % 0.001	1DX15 B ppm 1	1DX15 Al % 0.01	1DX15 Na % 0.001	1DX15 K % 0.01	1DX15 W ppm 0.1	1DX15 Hg ppm 0.01	1DX15 Sc ppm 0.1	1DX15 Ti ppm 0.1	1DX15 S % 0.05	1DX15 Ga ppm 1	1DX15 Se ppm 0.5	
774788	Drill Core	0.112	8	24	2.20	841	<0.001	7	0.65	0.076	0.26	<0.1	0.79	10.4	0.3	0.15	1	<0.5
774789	Drill Core	0.130	9	23	2.16	806	0.001	6	0.66	0.076	0.31	<0.1	0.01	11.8	0.1	<0.05	1	<0.5
774790	Drill Core	0.135	10	43	1.88	735	0.010	9	0.74	0.088	0.34	0.1	0.03	10.5	0.2	<0.05	2	<0.5
774791	Drill Core	0.137	14	78	2.11	315	0.015	5	1.12	0.104	0.27	<0.1	0.02	11.3	0.2	<0.05	5	<0.5
774792	Drill Core	0.130	14	68	2.24	2087	0.006	6	1.26	0.101	0.27	<0.1	0.01	11.0	0.1	0.06	6	<0.5
774793	Drill Core	0.135	15	83	1.72	800	0.015	5	1.28	0.080	0.24	<0.1	0.02	11.1	0.3	0.05	6	<0.5
774794	Drill Core	0.133	14	80	1.81	1314	0.014	7	2.41	0.070	0.23	<0.1	0.01	8.8	0.3	0.08	9	<0.5
774795	Drill Core	0.142	15	98	2.29	234	0.159	6	1.96	0.076	0.14	0.2	<0.01	8.6	<0.1	<0.05	9	<0.5
774796	Drill Core	0.124	14	104	2.18	30	0.160	8	1.72	0.110	0.06	0.3	0.02	9.5	<0.1	<0.05	11	<0.5
774797	Drill Core	0.141	13	106	1.55	65	0.292	24	2.08	0.087	0.05	0.3	<0.01	6.6	<0.1	<0.05	12	<0.5
774798	Drill Core	0.142	13	105	2.32	30	0.290	14	2.33	0.102	0.08	<0.1	<0.01	5.6	<0.1	<0.05	9	<0.5
774799	Drill Core	0.141	11	23	2.88	352	0.002	3	0.78	0.026	0.17	<0.1	0.05	12.5	<0.1	0.17	2	<0.5
774800	Drill Core	0.061	5	39	10.13	14	0.121	6	0.93	0.040	0.04	<0.1	<0.01	2.6	<0.1	<0.05	4	<0.5
774801	Drill Core	0.115	6	44	3.71	134	<0.001	7	0.54	0.012	0.20	<0.1	0.11	13.7	<0.1	0.11	1	<0.5
774802	Drill Core	0.124	7	45	3.49	101	<0.001	7	0.66	0.014	0.25	<0.1	0.09	16.4	0.1	0.10	1	<0.5
774803	Drill Core	0.128	6	49	2.98	126	<0.001	7	0.62	0.013	0.23	<0.1	0.07	16.3	<0.1	0.06	1	<0.5
774804	Drill Core	0.111	5	50	3.48	93	0.001	5	0.52	0.014	0.21	<0.1	0.36	14.4	<0.1	<0.05	1	<0.5
774805	Drill Core	0.108	5	46	2.63	102	<0.001	5	0.57	0.012	0.22	<0.1	0.40	14.6	<0.1	0.06	1	<0.5
774806	Drill Core	0.112	5	47	2.99	90	<0.001	6	0.53	0.012	0.19	<0.1	0.19	14.9	<0.1	0.05	<1	<0.5
774807	Drill Core	0.103	5	42	2.90	64	<0.001	7	0.52	0.010	0.20	<0.1	0.13	12.9	<0.1	0.05	1	<0.5
774808	Drill Core	0.128	5	50	2.70	71	<0.001	7	0.55	0.011	0.21	<0.1	0.43	15.4	<0.1	0.08	1	0.5
RRE 774808	Drill Core	0.122	5	49	2.66	73	<0.001	6	0.53	0.011	0.20	<0.1	0.45	15.6	<0.1	0.09	<1	<0.5
774809	Drill Core	0.121	5	52	2.09	68	<0.001	7	0.58	0.012	0.23	<0.1	0.31	15.4	<0.1	0.10	1	<0.5
774810	Drill Core	0.153	5	60	2.29	74	<0.001	7	0.62	0.012	0.25	0.2	0.38	18.6	<0.1	0.22	1	<0.5
774811	Drill Core	0.062	6	13	0.92	91	<0.001	5	0.47	0.009	0.26	0.1	0.40	8.5	0.2	0.92	<1	0.5
774812	Drill Core	0.042	4	13	1.48	75	<0.001	6	0.40	0.008	0.21	0.1	0.34	7.9	<0.1	0.56	<1	0.6
774813	Drill Core	0.099	5	41	2.06	125	<0.001	7	0.52	0.010	0.21	0.2	0.27	12.9	0.1	0.29	1	<0.5
774814	Drill Core	0.111	13	52	1.43	182	0.073	6	1.25	0.060	0.14	0.1	<0.01	8.4	<0.1	<0.05	5	<0.5
774815	Drill Core	0.052	2	16	0.80	92	<0.001	4	0.46	0.008	0.25	<0.1	0.56	9.1	<0.1	0.82	1	0.7
774816	Drill Core	0.057	3	17	0.81	93	<0.001	7	0.51	0.010	0.27	0.1	0.28	9.6	<0.1	0.71	1	0.6



852 E. Hastings St. Vancouver BC V6A 1R6 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

ACME ANALYTICAL LABORATORIES LTD.

www.acmelab.com

Client:

Cadillac Mining Exploration

3741 W. 36th Ave  
 Vancouver BC V6N 2S3 Canada

Project:

Silver Streak

Report Date:

February 26, 2008

Page:

6 of 8

Part 1

# CERTIFICATE OF ANALYSIS

SMI08000468.1

Method	WGHT	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15
Analyte	Wgt	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
774817	Drill Core	4.50	6.5	275.3	281.1	365	22.1	101.4	32.1	1266	4.12	220.9	0.3	<0.5	2.6	77	3.2	78.3	0.3	32	1.14
774818	Drill Core	3.60	3.0	217.3	2142	942	23.8	96.7	32.3	1104	4.66	201.0	0.4	<0.5	3.0	65	8.7	59.1	0.3	36	1.28
774819	Drill Core	2.60	4.9	252.0	301.3	447	22.7	99.5	26.7	2023	4.69	196.8	0.3	<0.5	2.5	85	3.9	73.7	0.3	41	1.73
774820	Drill Core	0.90	0.1	3.5	3.1	16	<0.1	1.4	0.9	217	0.38	0.6	1.2	<0.5	0.1	53	<0.1	0.5	<0.1	<2	26.26
774821	Drill Core	1.60	4.4	730.7	1196	1145	49.7	104.7	35.4	1800	5.42	345.6	0.3	<0.5	2.1	105	13.7	216.3	0.3	36	2.62
774822	Drill Core	3.40	1.8	33.6	93.7	202	0.4	37.8	11.1	272	2.08	65.2	0.4	<0.5	1.0	60	1.1	3.0	0.1	23	1.99
774823	Drill Core	1.00	1.9	25.7	41.5	104	0.3	26.7	7.6	235	1.76	99.9	0.3	<0.5	0.9	54	0.5	2.7	<0.1	17	1.83
774824	Drill Core	0.20	3.1	36.8	41.8	143	0.4	43.7	12.0	258	2.05	72.1	0.5	<0.5	1.1	66	1.0	4.5	0.1	20	1.58
774825	Drill Core	4.30	3.1	38.0	52.5	227	0.4	41.4	11.1	295	2.24	68.2	0.5	<0.5	1.0	71	1.2	3.9	0.1	25	2.02
774826	Drill Core	4.20	1.8	31.7	28.2	248	0.5	35.4	11.7	488	2.94	118.4	0.4	<0.5	1.1	90	1.4	2.9	<0.1	31	3.04
774827	Drill Core	2.40	3.6	40.8	136.7	518	1.1	49.9	23.6	632	4.14	249.6	0.6	<0.5	1.5	124	3.5	4.0	0.2	50	3.68
774828	Drill Core	2.60	1.7	16.7	66.7	198	0.4	35.5	11.6	760	2.77	76.1	1.0	<0.5	1.4	365	1.3	1.9	<0.1	35	20.39
774829	Drill Core	4.60	0.4	18.8	386.0	199	1.9	52.6	18.5	1049	3.27	60.0	0.6	<0.5	1.2	334	1.4	4.5	<0.1	38	20.33
774830	Drill Core	2.80	0.6	70.0	2632	1761	11.1	68.1	29.7	3660	6.12	68.7	0.2	<0.5	1.2	134	12.6	15.8	<0.1	69	6.72
774831	Drill Core	3.20	1.4	67.1	933.9	1610	5.0	63.8	28.1	3807	6.86	55.4	0.1	<0.5	0.9	125	11.6	12.0	<0.1	91	7.49
774832	Drill Core	5.20	0.6	21.7	121.6	330	1.3	57.0	17.3	549	3.76	65.0	0.3	<0.5	1.5	216	2.4	4.2	<0.1	28	10.58
774833	Drill Core	5.10	0.4	20.0	183.6	559	1.5	52.1	18.3	609	4.23	58.3	0.6	<0.5	1.3	208	4.7	3.7	<0.1	32	10.84
774834	Drill Core	5.20	1.5	68.4	1132	1040	6.4	53.6	22.3	1155	4.12	84.9	0.5	<0.5	1.2	199	8.3	15.6	<0.1	24	11.36
774835	Drill Core	3.50	1.0	28.0	230.2	294	1.1	67.0	26.0	563	4.62	88.5	0.5	<0.5	1.2	208	2.1	2.4	<0.1	29	9.89
774836	Drill Core	3.80	0.1	5.7	21.2	107	<0.1	79.3	28.7	1102	5.54	17.3	0.1	2.6	1.4	183	0.4	0.4	<0.1	43	10.06
774837	Drill Core	3.40	0.1	5.3	19.5	114	<0.1	85.7	25.6	606	5.64	15.4	0.1	0.9	1.7	166	0.3	0.4	<0.1	46	4.62
774838	Drill Core	3.20	<0.1	11.1	8.8	112	<0.1	71.1	26.0	799	4.78	9.3	0.1	<0.5	1.6	170	0.4	0.8	<0.1	47	5.52
774839	Drill Core	2.20	0.1	21.3	8.5	86	<0.1	50.5	23.7	617	3.89	1.6	0.1	0.5	1.3	164	0.3	0.2	<0.1	39	3.60
774840	Drill Core	0.60	0.2	1.1	1.4	13	<0.1	0.8	0.7	168	0.34	0.6	0.8	<0.5	<0.1	40	<0.1	<0.1	<0.1	<2	23.12
774841	Drill Core	3.40	0.3	3.8	8.5	91	<0.1	49.0	22.7	844	3.96	1.4	0.3	<0.5	1.3	113	0.4	0.4	<0.1	77	5.25
774842	Drill Core	2.60	0.3	4.1	11.3	82	<0.1	34.4	18.1	513	3.78	2.7	0.3	<0.5	1.2	132	0.5	1.1	<0.1	55	3.68
774843	Drill Core	2.20	0.2	4.7	11.2	150	<0.1	44.9	22.9	499	3.35	1.5	0.2	<0.5	1.1	124	0.7	0.7	<0.1	70	3.68
774844	Drill Core	2.60	0.2	3.4	14.6	135	<0.1	30.2	14.7	414	3.56	2.4	0.2	<0.5	0.8	130	0.6	1.2	<0.1	33	2.53
774845	Drill Core	4.00	0.2	11.4	8.4	107	<0.1	45.7	17.9	575	3.86	2.0	<0.1	<0.5	1.1	117	0.5	0.7	<0.1	41	4.13
RRE 774845	Drill Core		0.2	11.0	8.5	109	<0.1	45.4	18.1	577	3.88	2.0	<0.1	<0.5	1.1	117	0.4	0.7	<0.1	41	4.12



ACME ANALYTICAL LABORATORIES LTD.  
 852 E. Hastings St. Vancouver BC V6A 1R6 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Cadillac Mining Exploration

3741 W. 36th Ave  
 Vancouver BC V6N 2S3 Canada

Project: Silver Streak

Report Date: February 26, 2008

Page: 6 of 8 Part 2

# CERTIFICATE OF ANALYSIS

SMI08000468.1

Method Analyte Unit MDL	1DX15 P % 0.001	1DX15 La ppm 1	1DX15 Cr ppm 1	1DX15 Mg % 0.01	1DX15 Ba ppm 1	1DX15 Ti % 0.001	1DX15 B ppm 1	1DX15 Al % 0.01	1DX15 Na % 0.001	1DX15 K % 0.01	1DX15 W ppm 0.1	1DX15 Hg ppm 0.01	1DX15 Sc ppm 0.1	1DX15 Ti ppm 0.1	1DX15 S % 0.05	1DX15 Ga ppm 1	1DX15 Se ppm 0.5	
774817	Drill Core	0.060	2	15	0.73	111	<0.001	5	0.49	0.009	0.27	0.1	0.14	9.6	<0.1	0.30	<1	0.6
774818	Drill Core	0.067	2	17	0.81	93	<0.001	7	0.53	0.010	0.30	0.1	0.24	10.5	<0.1	0.65	1	<0.5
774819	Drill Core	0.069	2	22	0.87	106	<0.001	8	0.58	0.012	0.27	0.1	0.18	11.4	<0.1	0.24	1	<0.5
774820	Drill Core	0.019	<1	1	12.74	12	0.001	<1	0.06	0.002	0.03	<0.1	<0.01	0.3	<0.1	<0.05	<1	<0.5
774821	Drill Core	0.051	1	14	1.07	117	0.001	5	0.52	0.010	0.25	1.2	0.32	11.9	0.2	0.87	1	<0.5
774822	Drill Core	0.033	1	12	0.59	38	<0.001	4	0.40	0.028	0.16	<0.1	0.10	6.2	<0.1	1.00	1	1.4
774823	Drill Core	0.022	1	10	0.54	28	<0.001	3	0.29	0.027	0.11	<0.1	0.08	5.4	<0.1	0.81	<1	1.1
774824	Drill Core	0.033	1	11	0.50	31	<0.001	5	0.39	0.033	0.15	<0.1	0.10	7.4	0.1	1.39	<1	1.8
774825	Drill Core	0.026	1	16	0.62	36	<0.001	5	0.36	0.043	0.15	<0.1	0.12	6.4	<0.1	1.46	<1	2.3
774826	Drill Core	0.041	4	17	0.86	63	<0.001	4	0.43	0.043	0.15	<0.1	0.11	7.5	<0.1	1.26	<1	1.0
774827	Drill Core	0.083	6	22	0.89	101	<0.001	5	0.69	0.065	0.23	<0.1	0.17	12.4	0.1	2.08	2	1.8
774828	Drill Core	0.171	14	28	0.73	135	<0.001	7	0.58	0.063	0.21	<0.1	0.08	7.9	<0.1	0.96	1	<0.5
774829	Drill Core	0.131	15	25	0.98	284	<0.001	8	0.57	0.058	0.21	<0.1	0.06	9.0	<0.1	0.56	1	0.7
774830	Drill Core	0.158	8	29	1.10	110	0.001	10	0.82	0.064	0.28	<0.1	0.48	16.7	<0.1	0.83	1	<0.5
774831	Drill Core	0.174	8	37	1.68	112	0.001	8	0.83	0.068	0.27	0.1	0.09	17.0	<0.1	0.13	1	<0.5
774832	Drill Core	0.112	12	24	0.80	141	<0.001	9	0.83	0.087	0.29	<0.1	0.07	10.5	0.1	0.49	1	<0.5
774833	Drill Core	0.189	14	28	0.58	130	<0.001	12	1.00	0.106	0.35	<0.1	0.12	9.5	0.2	0.45	2	<0.5
774834	Drill Core	0.156	11	24	0.77	85	0.001	8	0.80	0.095	0.28	<0.1	0.16	8.9	0.2	0.82	1	1.0
774835	Drill Core	0.199	13	27	0.68	164	<0.001	6	0.93	0.150	0.29	<0.1	0.07	9.8	0.2	0.65	2	<0.5
774836	Drill Core	0.092	8	30	0.81	123	<0.001	6	0.41	0.167	0.17	<0.1	0.02	10.5	<0.1	<0.05	<1	<0.5
774837	Drill Core	0.092	7	24	1.01	427	<0.001	7	0.52	0.220	0.21	<0.1	0.02	13.0	<0.1	<0.05	<1	<0.5
774838	Drill Core	0.059	8	25	1.14	1198	<0.001	5	0.43	0.198	0.19	<0.1	0.02	13.0	<0.1	<0.05	<1	<0.5
774839	Drill Core	0.086	8	20	0.98	1549	0.002	5	0.51	0.219	0.19	<0.1	<0.01	11.3	<0.1	<0.05	<1	<0.5
774840	Drill Core	0.015	<1	<1	11.84	12	<0.001	1	0.02	0.001	0.01	<0.1	<0.01	0.3	<0.1	<0.05	<1	<0.5
774841	Drill Core	0.102	11	31	1.23	100	0.004	5	0.51	0.166	0.19	<0.1	<0.01	10.6	<0.1	<0.05	<1	<0.5
774842	Drill Core	0.055	8	29	1.07	104	0.006	6	0.51	0.205	0.20	<0.1	<0.01	11.6	<0.1	<0.05	<1	<0.5
774843	Drill Core	0.090	10	21	1.16	189	0.003	5	0.50	0.171	0.21	<0.1	0.03	10.0	<0.1	<0.05	<1	<0.5
774844	Drill Core	0.024	6	22	0.80	177	0.006	6	0.51	0.213	0.22	<0.1	<0.01	10.6	<0.1	<0.05	1	<0.5
774845	Drill Core	0.073	8	30	1.41	589	0.021	5	0.43	0.149	0.18	<0.1	<0.01	11.2	<0.1	<0.05	<1	<0.5
RRE 774845	Drill Core	0.073	8	30	1.42	529	0.019	5	0.43	0.148	0.18	<0.1	<0.01	11.3	<0.1	<0.05	<1	<0.5





ACME ANALYTICAL LABORATORIES LTD.  
 852 E. Hastings St. Vancouver BC V6A 1R6 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Cadillac Mining Exploration

3741 W. 36th Ave  
 Vancouver BC V6N 2S3 Canada

Project: Silver Streak

Report Date: February 26, 2008

Page: 7 of 8 Part 1

CERTIFICATE OF ANALYSIS

SMI08000468.1

Method Analyte Unit MDL	WGHT	1DX15 Mo	1DX15 Cu	1DX15 Pb	1DX15 Zn	1DX15 Ag	1DX15 Ni	1DX15 Co	1DX15 Mn	1DX15 Fe	1DX15 As	1DX15 U	1DX15 Au	1DX15 Th	1DX15 Sr	1DX15 Cd	1DX15 Sb	1DX15 Bi	1DX15 V	1DX15 Ca	
	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
	0.01	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
774846	Drill Core	3.00	0.2	4.5	9.6	125	<0.1	47.7	19.9	718	3.70	2.1	0.1	0.6	1.1	102	0.7	0.7	<0.1	87	5.12
774847	Drill Core	1.70	0.2	5.3	10.7	124	<0.1	38.6	15.3	678	3.73	2.5	0.2	<0.5	1.3	87	0.7	0.9	<0.1	68	4.67
774848	Drill Core	0.80	0.2	2.6	9.5	180	<0.1	52.3	20.2	876	3.47	1.4	0.2	<0.5	0.9	103	0.9	0.5	<0.1	63	6.33
774849	Drill Core	0.50	0.5	121.6	16.6	336	2.7	71.8	24.3	1296	3.78	3.0	0.1	<0.5	1.0	108	1.6	4.1	<0.1	55	7.16
774850	Drill Core	2.30	0.2	7.2	14.3	170	<0.1	39.5	15.1	644	3.89	3.1	0.1	<0.5	1.2	85	0.9	1.1	<0.1	51	4.01
774851	Drill Core	1.70	0.2	2.7	20.7	359	<0.1	53.2	19.9	749	3.64	1.7	0.2	0.8	1.0	88	2.0	1.0	<0.1	61	4.27
774852	Drill Core	3.90	0.2	3.3	15.1	219	0.1	51.8	18.7	931	3.74	2.4	0.2	<0.5	1.2	81	1.0	0.7	<0.1	71	4.96
774853	Drill Core	2.40	0.2	15.5	15.6	319	0.7	52.4	19.1	1195	3.23	2.9	0.2	0.9	1.2	107	1.9	5.2	<0.1	67	5.17
774854	Drill Core	4.20	0.1	32.3	14.9	290	1.3	63.0	23.0	1199	3.39	3.1	0.1	<0.5	1.0	121	1.8	3.3	<0.1	67	5.48
774855	Drill Core	3.40	0.2	3.2	10.3	195	<0.1	44.1	16.3	1060	3.68	2.4	0.2	<0.5	1.2	78	1.0	1.0	<0.1	55	4.93
774856	Drill Core	2.50	0.2	6.2	16.7	203	<0.1	45.5	15.6	842	3.46	2.6	0.2	<0.5	1.4	91	1.2	1.1	<0.1	62	4.45
774857	Drill Core	1.50	1.2	108.0	1054	253	7.1	54.8	23.3	1148	3.41	14.3	0.2	0.5	1.4	123	1.8	14.8	<0.1	64	5.74
774858	Drill Core	0.90	0.1	2.6	19.5	146	0.3	40.2	19.0	802	3.33	2.4	0.2	<0.5	1.4	85	0.8	0.9	<0.1	85	4.71
774859	Drill Core	0.90	0.1	139.0	19.5	226	2.1	49.7	22.5	1242	3.52	1.1	0.1	0.5	1.2	121	1.3	0.6	<0.1	70	6.42
774860	Drill Core	0.80	<0.1	0.6	1.4	17	<0.1	1.1	0.7	179	0.35	<0.5	1.0	<0.5	<0.1	46	0.1	<0.1	<0.1	<2	23.40
774861	Drill Core	3.00	0.2	15.8	19.4	145	0.3	36.7	15.5	697	3.62	2.0	0.2	<0.5	1.3	120	0.7	1.8	<0.1	53	4.69
774862	Drill Core	2.20	0.1	2.9	16.4	144	0.1	41.5	20.5	834	3.13	1.3	0.3	0.5	1.4	127	0.8	0.9	<0.1	71	6.41
774863	Drill Core	3.50	0.2	4.4	22.6	109	<0.1	30.5	13.4	546	3.18	2.2	0.2	0.5	1.3	125	0.6	1.3	<0.1	47	4.64
774864	Drill Core	3.00	0.2	5.7	20.6	153	<0.1	37.6	17.2	686	3.49	2.3	0.2	1.0	1.3	154	0.7	1.3	<0.1	47	4.83
774865	Drill Core	4.10	0.2	10.4	21.4	183	<0.1	45.2	20.6	1068	3.71	2.4	0.2	<0.5	1.4	156	1.0	1.1	<0.1	70	6.26
774866	Drill Core	0.29	0.1	31.4	26.7	238	0.4	44.0	19.4	1156	3.12	3.7	0.2	<0.5	1.2	170	0.9	0.8	<0.1	56	5.91
774867	Drill Core	5.10	0.1	4.1	26.8	207	<0.1	44.7	21.2	860	3.95	2.9	0.2	<0.5	1.2	158	1.0	1.0	<0.1	70	4.57
774868	Drill Core	2.60	2.7	31.8	101.8	341	0.3	39.6	11.2	216	2.29	82.0	0.3	<0.5	0.8	54	2.2	4.0	<0.1	20	1.64
774869	Drill Core	2.80	0.2	1.7	22.7	200	<0.1	46.6	21.5	842	3.56	4.7	0.2	<0.5	1.4	149	0.9	1.1	<0.1	75	4.70
774870	Drill Core	2.40	1.8	28.6	32.9	176	0.1	36.6	10.5	219	1.99	65.5	0.3	<0.5	0.8	61	0.7	4.0	0.1	20	1.96
774871	Drill Core	1.10	2.9	30.6	87.1	362	0.5	36.3	9.2	228	2.21	61.7	0.3	<0.5	0.8	56	2.5	6.2	0.1	19	2.01
774872	Drill Core	3.60	2.0	38.0	57.8	309	0.2	38.0	10.8	270	2.35	96.8	0.2	1.8	0.6	65	1.6	9.5	0.1	20	2.37
774873	Drill Core	4.20	3.4	32.1	55.4	203	0.5	41.1	10.9	228	2.10	63.0	0.4	0.5	0.9	54	1.5	4.9	0.1	20	1.88
774874	Drill Core	0.40	2.8	25.8	67.7	328	0.9	31.0	8.0	322	2.07	50.1	0.3	0.7	0.5	57	1.9	4.2	0.1	17	2.85
774875	Drill Core	2.60	2.6	35.6	520.4	1018	3.3	38.8	10.6	389	1.91	72.4	0.4	<0.5	0.7	40	8.6	10.3	0.1	18	1.70



ACME ANALYTICAL LABORATORIES LTD.  
 852 E. Hastings St. Vancouver BC V6A 1R6 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Cadillac Mining Exploration

3741 W. 36th Ave  
 Vancouver BC V6N 2S3 Canada

Project: Silver Streak

Report Date: February 26, 2008

Page: 7 of 8 Part 2

# CERTIFICATE OF ANALYSIS

SMI08000468.1

Method	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	
774846	Drill Core	0.088	9	33	1.66	296	0.009	6	0.43	0.127	0.20	<0.1	0.02	11.5	<0.1	<0.05	<1	<0.5
774847	Drill Core	0.089	8	37	1.66	231	0.009	3	0.38	0.109	0.17	<0.1	0.02	12.4	<0.1	<0.05	<1	<0.5
774848	Drill Core	0.064	6	24	2.27	1593	0.003	4	0.34	0.085	0.17	<0.1	<0.01	10.6	<0.1	<0.05	<1	<0.5
774849	Drill Core	0.080	7	12	2.49	2426	0.001	4	0.36	0.092	0.18	<0.1	0.04	10.0	0.1	0.06	<1	<0.5
774850	Drill Core	0.064	7	32	1.40	343	0.014	6	0.42	0.110	0.22	<0.1	<0.01	10.8	<0.1	<0.05	<1	<0.5
774851	Drill Core	0.082	8	27	1.31	120	0.006	7	0.42	0.112	0.23	<0.1	0.02	11.9	<0.1	<0.05	<1	<0.5
774852	Drill Core	0.089	8	38	1.79	367	0.011	6	0.41	0.092	0.22	<0.1	<0.01	12.7	<0.1	<0.05	<1	<0.5
774853	Drill Core	0.096	8	17	1.70	2356	<0.001	7	0.35	0.077	0.21	<0.1	0.01	12.1	<0.1	0.06	<1	<0.5
774854	Drill Core	0.107	7	17	1.57	1324	0.001	6	0.42	0.087	0.24	<0.1	0.01	12.2	<0.1	<0.05	<1	<0.5
774855	Drill Core	0.079	7	33	1.75	1014	0.008	8	0.37	0.076	0.21	<0.1	0.01	12.3	<0.1	<0.05	<1	<0.5
774856	Drill Core	0.097	8	31	1.44	903	0.006	7	0.44	0.100	0.24	<0.1	0.02	13.2	<0.1	<0.05	<1	<0.5
774857	Drill Core	0.099	8	18	1.74	1378	<0.001	9	0.41	0.095	0.22	<0.1	0.05	12.9	0.1	0.09	<1	<0.5
774858	Drill Core	0.106	11	29	1.43	356	0.004	8	0.53	0.109	0.26	<0.1	0.04	12.8	0.1	<0.05	<1	<0.5
774859	Drill Core	0.100	9	17	1.89	1110	0.001	8	0.58	0.125	0.28	<0.1	0.04	13.1	0.2	<0.05	1	<0.5
774860	Drill Core	0.015	<1	<1	12.02	12	<0.001	<1	0.03	0.002	0.02	<0.1	<0.01	0.2	<0.1	<0.05	<1	<0.5
774861	Drill Core	0.096	10	16	1.45	707	0.005	7	0.58	0.121	0.28	<0.1	0.01	11.2	0.2	<0.05	<1	<0.5
774862	Drill Core	0.108	11	17	1.48	217	0.002	6	0.57	0.117	0.28	<0.1	0.02	11.6	<0.1	<0.05	1	<0.5
774863	Drill Core	0.087	10	17	1.25	100	0.006	6	0.57	0.137	0.28	<0.1	0.01	10.4	<0.1	<0.05	<1	<0.5
774864	Drill Core	0.092	10	17	1.63	444	0.003	7	0.67	0.142	0.30	<0.1	0.03	10.2	0.2	<0.05	1	<0.5
774865	Drill Core	0.115	11	25	2.28	523	0.006	10	0.61	0.114	0.28	<0.1	0.03	9.1	0.1	<0.05	<1	<0.5
774866	Drill Core	0.109	9	17	2.52	209	0.001	9	0.87	0.102	0.23	<0.1	0.13	9.4	0.1	<0.05	2	<0.5
774867	Drill Core	0.090	8	22	2.52	197	0.005	9	0.55	0.107	0.24	<0.1	0.03	9.1	<0.1	<0.05	<1	<0.5
774868	Drill Core	0.031	1	10	0.56	38	<0.001	4	0.31	0.022	0.14	<0.1	0.12	6.2	<0.1	1.38	<1	1.6
774869	Drill Core	0.114	10	22	2.40	93	0.005	8	0.55	0.117	0.25	<0.1	<0.01	9.2	<0.1	<0.05	<1	<0.5
774870	Drill Core	0.031	1	10	0.62	34	<0.001	4	0.27	0.021	0.13	<0.1	0.10	6.2	<0.1	0.99	<1	1.6
774871	Drill Core	0.026	<1	7	0.62	32	<0.001	4	0.26	0.022	0.12	<0.1	0.13	6.1	<0.1	1.19	<1	1.2
774872	Drill Core	0.031	<1	10	0.77	26	<0.001	2	0.26	0.018	0.11	<0.1	0.16	6.6	<0.1	1.15	<1	1.4
774873	Drill Core	0.031	1	9	0.57	38	<0.001	3	0.25	0.025	0.13	<0.1	0.12	6.9	<0.1	1.28	<1	1.4
774874	Drill Core	0.020	<1	8	0.62	34	<0.001	3	0.21	0.023	0.10	<0.1	0.11	5.6	<0.1	0.91	<1	1.6
774875	Drill Core	0.027	1	10	0.52	43	<0.001	5	0.25	0.030	0.13	<0.1	0.17	5.9	<0.1	1.01	<1	1.1



ACME ANALYTICAL LABORATORIES LTD.  
 852 E. Hastings St. Vancouver BC V6A 1R6 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Cadillac Mining Exploration

3741 W. 36th Ave  
 Vancouver BC V6N 2S3 Canada

Project: Silver Streak

Report Date: February 26, 2008

Page: 8 of 8 Part 1

# CERTIFICATE OF ANALYSIS

SMI08000468.1

Method	WGHT	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	
Analyte	Wgt	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
RRE 774875	Drill Core		2.8	41.9	595.3	1206	3.7	38.7	10.8	413	1.99	78.3	0.4	<0.5	0.8	41	9.9	12.0	0.1	19	1.79
774876	Drill Core	2.80	1.3	36.2	127.9	825	2.8	41.0	18.0	546	4.79	76.7	1.4	<0.5	1.2	97	6.6	7.0	0.1	56	3.62
774877	Drill Core	1.50	0.8	9.3	54.6	193	0.3	31.6	11.3	682	2.70	65.0	0.7	<0.5	1.1	369	1.6	1.7	<0.1	31	20.93
774878	Drill Core	1.70	0.5	11.8	46.6	170	0.3	41.8	13.9	672	2.77	59.7	0.5	2.6	1.0	338	0.9	2.1	<0.1	31	22.82
774879	Drill Core	1.50	0.3	13.5	37.9	130	0.1	43.5	13.9	730	3.22	41.5	0.9	0.8	1.5	416	0.9	1.9	<0.1	36	22.59
774880	Drill Core	0.70	<0.1	1.0	1.3	14	<0.1	1.7	0.5	198	0.38	0.6	0.8	<0.5	<0.1	42	0.1	<0.1	<0.1	<2	25.33
774881	Drill Core	1.50	0.4	13.0	44.2	143	0.1	44.1	14.6	667	2.89	40.3	0.6	1.4	1.4	404	0.8	1.9	<0.1	36	22.51
774882	Drill Core	1.70	0.3	11.2	52.4	168	0.3	41.6	13.8	711	2.78	47.2	0.4	<0.5	1.0	354	1.0	2.1	<0.1	29	22.44
774883	Drill Core	1.40	1.0	13.7	82.5	185	0.7	50.6	16.2	737	3.12	56.3	0.4	<0.5	1.1	370	1.3	2.7	<0.1	30	21.32
774884	Drill Core	1.30	2.2	49.6	210.9	668	4.2	40.8	15.0	1409	3.11	37.7	0.3	<0.5	1.1	328	6.3	5.1	<0.1	24	21.72
774885	Drill Core	1.90	0.7	29.6	107.3	210	1.5	52.2	20.6	1049	2.73	67.1	0.4	0.6	1.1	367	1.5	5.0	<0.1	30	21.82
774886	Drill Core	1.60	0.9	13.2	32.9	119	0.2	43.7	18.2	1296	2.05	69.5	0.3	1.3	1.0	358	0.8	1.9	<0.1	23	23.64
774887	Drill Core	1.60	0.4	17.5	27.2	98	0.1	46.6	19.6	1378	2.62	52.0	0.2	<0.5	1.1	315	0.5	1.7	<0.1	24	20.86
774888	Drill Core	3.60	0.4	46.1	9.6	94	<0.1	38.0	25.1	1065	5.21	42.1	0.1	1.4	0.8	219	0.4	2.1	<0.1	66	10.11
774889	Drill Core	3.00	0.3	33.3	7.5	61	<0.1	39.9	23.8	897	5.81	44.5	0.1	<0.5	0.8	211	0.2	1.4	<0.1	64	9.51
774890	Drill Core	2.50	0.3	21.9	13.9	72	<0.1	54.8	21.9	663	3.86	72.5	0.3	<0.5	1.5	282	0.3	1.0	<0.1	40	14.06
774891	Drill Core	2.50	0.4	16.9	10.7	97	<0.1	42.0	15.0	554	3.52	61.8	0.2	<0.5	1.3	297	0.5	0.6	<0.1	31	15.05
774892	Drill Core	0.30	1.8	23.7	40.5	73	0.2	85.1	20.6	465	4.84	113.5	0.3	<0.5	1.3	338	0.4	1.1	<0.1	22	16.98



ACME ANALYTICAL LABORATORIES LTD.  
 852 E. Hastings St. Vancouver BC V6A 1R6 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Cadillac Mining Exploration

3741 W. 36th Ave  
 Vancouver BC V6N 2S3 Canada

Project: Silver Streak

Report Date: February 26, 2008

Page: 8 of 8 Part 2

# CERTIFICATE OF ANALYSIS

SMI08000468.1

Method	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	
RRE 774875	Drill Core	0.028	1	11	0.52	41	<0.001	4	0.26	0.031	0.13	<0.1	0.18	6.3	<0.1	1.04	<1	2.2
774876	Drill Core	0.298	11	35	0.92	68	0.002	8	0.76	0.051	0.31	0.6	0.19	11.8	0.1	2.59	2	1.4
774877	Drill Core	0.174	13	20	0.73	148	<0.001	4	0.37	0.049	0.16	<0.1	0.05	7.6	<0.1	0.79	<1	<0.5
774878	Drill Core	0.140	15	21	0.67	260	0.001	6	0.37	0.047	0.16	0.2	0.04	8.0	<0.1	0.49	<1	<0.5
774879	Drill Core	0.184	19	23	0.65	195	0.001	7	0.51	0.073	0.20	<0.1	0.02	8.8	<0.1	0.21	<1	<0.5
774880	Drill Core	0.014	<1	<1	12.47	8	<0.001	<1	0.02	<0.001	0.02	<0.1	<0.01	0.2	<0.1	<0.05	<1	<0.5
774881	Drill Core	0.166	19	21	0.60	859	0.001	10	0.53	0.082	0.21	<0.1	0.02	9.6	<0.1	0.21	1	<0.5
774882	Drill Core	0.112	14	17	0.68	382	<0.001	5	0.36	0.054	0.16	<0.1	0.03	7.6	<0.1	0.23	<1	<0.5
774883	Drill Core	0.098	13	19	0.71	142	<0.001	6	0.36	0.065	0.16	<0.1	0.04	7.9	0.1	0.62	<1	0.5
774884	Drill Core	0.077	12	15	0.80	120	<0.001	6	0.33	0.047	0.16	<0.1	0.11	8.1	<0.1	1.01	<1	<0.5
774885	Drill Core	0.093	14	18	0.96	119	0.001	7	0.37	0.055	0.16	<0.1	0.04	8.3	<0.1	0.25	<1	<0.5
774886	Drill Core	0.073	12	13	0.84	92	<0.001	5	0.30	0.053	0.13	<0.1	0.02	7.7	<0.1	0.19	<1	<0.5
774887	Drill Core	0.080	11	13	1.01	89	<0.001	5	0.35	0.076	0.15	<0.1	0.01	8.3	<0.1	0.09	<1	<0.5
774888	Drill Core	0.153	10	15	1.70	125	<0.001	4	0.63	0.137	0.19	<0.1	0.02	16.3	<0.1	0.09	1	<0.5
774889	Drill Core	0.188	12	22	1.67	132	0.001	4	0.75	0.169	0.21	<0.1	<0.01	17.0	<0.1	0.07	1	<0.5
774890	Drill Core	0.179	15	21	1.15	133	<0.001	6	0.52	0.154	0.16	<0.1	0.02	9.6	<0.1	0.13	<1	<0.5
774891	Drill Core	0.131	14	15	0.98	102	0.002	5	0.57	0.167	0.20	<0.1	0.03	8.9	0.1	0.24	<1	<0.5
774892	Drill Core	0.098	14	16	1.01	100	<0.001	4	0.46	0.176	0.17	<0.1	0.13	8.3	0.2	1.77	<1	0.7

**Client:** Cadillac Mining Exploration  
3741 W. 36th Ave  
Vancouver BC V6N 2S3 Canada

**Project:** Silver Streak  
**Report Date:** February 26, 2008

www.acmelab.com

**Page:** 1 of 2 **Part** 1

## QUALITY CONTROL REPORT

**SMI08000468.1**

Method		WGHT	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15
Analyte	Unit	Wgt	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
	MDL	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
	MDL	0.01	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	0.1	2	0.01
Pulp Duplicates																						
774711	Drill Core	1.40	1.0	26.5	35.1	167	0.1	51.7	25.5	489	3.02	98.1	0.2	<0.5	1.3	97	0.8	2.2	0.2	23	1.37	
REP 774711	QC		1.1	28.2	33.3	169	0.1	51.8	26.0	497	3.05	100.5	0.2	<0.5	1.3	97	0.9	2.3	0.2	22	1.40	
774756	Drill Core	4.70	0.3	11.9	15.4	77	<0.1	53.5	27.0	909	4.13	3.8	0.2	1.0	0.8	200	0.2	0.5	<0.1	78	4.11	
REP 774756	QC		0.4	12.9	15.4	72	<0.1	54.2	27.8	908	4.15	3.6	0.2	0.7	0.8	198	0.2	0.6	<0.1	77	4.08	
774797	Drill Core	1.50	0.8	35.1	7.0	67	<0.1	90.5	24.8	696	4.40	5.9	0.6	<0.5	1.4	57	0.1	<0.1	<0.1	136	4.26	
REP 774797	QC		0.7	33.3	6.7	62	<0.1	84.3	23.6	652	4.11	5.4	0.6	<0.5	1.2	55	0.2	<0.1	<0.1	130	4.04	
774821	Drill Core	1.60	4.4	730.7	1196	1145	49.7	104.7	35.4	1800	5.42	345.6	0.3	<0.5	2.1	105	13.7	216.3	0.3	36	2.62	
REP 774821	QC		4.2	678.4	1131	1096	45.5	106.8	34.1	1753	5.08	320.8	0.2	<0.5	1.9	100	13.0	185.9	0.3	34	2.41	
774867	Drill Core	5.10	0.1	4.1	26.8	207	<0.1	44.7	21.2	860	3.95	2.9	0.2	<0.5	1.2	158	1.0	1.0	<0.1	70	4.57	
REP 774867	QC		0.2	4.3	26.3	209	<0.1	44.3	21.2	868	3.97	3.1	0.2	<0.5	1.2	157	0.9	1.2	<0.1	71	4.49	
774873	Drill Core	4.20	3.4	32.1	55.4	203	0.5	41.1	10.9	228	2.10	63.0	0.4	0.5	0.9	54	1.5	4.9	0.1	20	1.88	
REP 774873	QC		3.4	32.0	55.6	206	0.5	39.8	10.7	224	2.06	63.0	0.4	<0.5	0.8	53	1.5	4.8	0.1	19	1.79	
Reference Materials																						
STD DS7	Standard		22.6	116.7	83.7	441	0.9	62.0	10.4	700	2.68	54.4	5.8	71.0	5.6	93	7.4	7.4	5.6	101	1.13	
STD DS7	Standard		20.5	108.6	78.1	404	0.9	56.5	9.8	634	2.45	49.5	5.5	85.4	5.6	85	6.4	6.8	5.1	90	1.02	
STD DS7	Standard		23.6	115.6	79.6	437	0.9	60.9	10.4	667	2.59	56.0	5.6	63.9	5.1	77	6.8	6.7	5.2	95	1.05	
STD DS7	Standard		20.8	108.6	74.2	422	0.9	58.5	10.1	624	2.43	53.9	5.2	64.4	4.6	76	6.4	6.7	5.1	89	0.99	
STD DS7	Standard		21.3	105.6	72.0	405	0.9	56.6	9.2	632	2.42	51.9	4.6	77.5	4.5	69	6.4	6.3	4.8	84	1.11	
STD DS7	Standard		21.5	105.8	73.8	400	0.9	57.3	9.6	635	2.44	52.5	5.1	73.9	5.0	75	7.0	6.3	4.9	87	1.00	
STD DS7	Standard		18.8	94.0	67.6	364	0.8	51.6	8.5	574	2.22	46.9	4.4	56.0	4.0	66	5.8	5.7	4.2	79	0.87	
STD DS7	Standard		18.4	95.2	69.0	372	0.8	51.2	8.5	576	2.21	46.8	4.7	57.8	4.1	64	6.1	5.7	4.4	79	0.88	
STD DS7	Standard		21.7	103.9	71.7	393	0.8	59.0	9.9	612	2.40	46.8	5.1	63.4	4.9	75	6.3	5.8	4.5	91	1.00	
STD DS7	Standard		21.2	101.3	69.3	376	0.8	58.5	9.6	606	2.35	45.1	5.1	65.5	4.8	74	5.9	5.9	4.2	88	0.99	
STD DS7	Standard		21.8	114.7	80.5	415	0.9	61.1	9.8	684	2.65	54.0	5.5	65.5	5.3	79	6.2	6.5	5.3	93	1.07	
STD DS7	Standard		22.5	107.5	76.7	425	1.0	60.0	10.3	711	2.62	53.2	5.6	73.0	5.4	80	6.8	6.3	5.3	93	1.04	
STD DS7 Expected			20.92	109	70.6	411	0.89	56	9.7	627	2.39	48.2	4.9	70	4.4	68.7	6.38	5.86	4.51	86	0.93	
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	



ACME ANALYTICAL LABORATORIES LTD.  
 852 E. Hastings St. Vancouver BC V6A 1R6 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Cadillac Mining Exploration

3741 W. 36th Ave  
 Vancouver BC V6N 2S3 Canada

Project: Silver Streak

Report Date: February 26, 2008

Page: 1 of 2 Part 2

QUALITY CONTROL REPORT

SMI08000468.1

Method	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	
Pulp Duplicates																		
774711	Drill Core	0.047	2	10	0.71	72	<0.001	8	0.57	0.075	0.27	<0.1	0.05	8.6	<0.1	0.86	1	0.8
REP 774711	QC	0.047	2	10	0.72	74	0.001	6	0.54	0.072	0.27	<0.1	0.07	8.7	<0.1	0.87	1	<0.5
774756	Drill Core	0.091	7	40	2.90	71	0.003	6	0.65	0.244	0.27	<0.1	<0.01	15.1	0.1	<0.05	<1	0.8
REP 774756	QC	0.088	7	42	2.87	72	0.004	7	0.71	0.235	0.29	<0.1	<0.01	15.0	0.1	<0.05	1	<0.5
774797	Drill Core	0.141	13	106	1.55	65	0.292	24	2.08	0.087	0.05	0.3	<0.01	6.6	<0.1	<0.05	12	<0.5
REP 774797	QC	0.132	13	99	1.44	63	0.275	24	1.98	0.088	0.05	0.3	<0.01	6.3	<0.1	<0.05	11	<0.5
774821	Drill Core	0.051	1	14	1.07	117	0.001	5	0.52	0.010	0.25	1.2	0.32	11.9	0.2	0.87	1	<0.5
REP 774821	QC	0.047	1	14	1.04	117	<0.001	6	0.54	0.010	0.26	1.1	0.30	11.7	0.2	0.81	1	0.7
774867	Drill Core	0.090	8	22	2.52	197	0.005	9	0.55	0.107	0.24	<0.1	0.03	9.1	<0.1	<0.05	<1	<0.5
REP 774867	QC	0.090	8	22	2.48	191	0.005	10	0.59	0.108	0.25	<0.1	0.04	9.3	0.1	<0.05	<1	<0.5
774873	Drill Core	0.031	1	9	0.57	38	<0.001	3	0.25	0.025	0.13	<0.1	0.12	6.9	<0.1	1.28	<1	1.4
REP 774873	QC	0.030	1	9	0.54	38	<0.001	4	0.25	0.024	0.13	<0.1	0.11	6.6	<0.1	1.24	<1	1.9
Reference Materials																		
STD DS7	Standard	0.083	17	224	1.21	427	0.153	44	1.19	0.106	0.50	4.3	0.22	2.9	4.9	0.22	6	4.5
STD DS7	Standard	0.074	16	205	1.06	390	0.138	42	1.11	0.101	0.45	3.8	0.23	2.7	4.4	0.20	5	4.0
STD DS7	Standard	0.083	14	215	1.15	423	0.129	54	1.10	0.105	0.51	4.3	0.24	2.3	4.7	0.21	5	3.9
STD DS7	Standard	0.081	12	198	1.07	391	0.116	47	1.01	0.093	0.45	4.2	0.22	2.0	4.4	0.20	4	3.1
STD DS7	Standard	0.079	13	198	1.12	418	0.113	42	1.00	0.093	0.45	4.0	0.19	2.4	4.4	0.19	5	3.1
STD DS7	Standard	0.082	14	198	1.08	442	0.120	44	1.06	0.097	0.46	4.2	0.20	2.7	4.6	0.20	5	3.8
STD DS7	Standard	0.074	11	177	0.97	376	0.101	38	0.90	0.085	0.41	3.6	0.18	2.3	4.1	0.19	5	2.8
STD DS7	Standard	0.073	11	179	0.97	372	0.099	38	0.92	0.083	0.42	3.9	0.18	2.2	4.4	0.19	4	2.5
STD DS7	Standard	0.076	13	220	1.06	369	0.124	40	1.05	0.090	0.42	3.7	0.20	2.5	4.1	0.20	5	3.6
STD DS7	Standard	0.074	13	211	1.04	364	0.124	36	1.06	0.086	0.41	3.6	0.19	2.5	4.2	0.19	5	3.4
STD DS7	Standard	0.083	14	222	1.16	418	0.131	46	1.13	0.100	0.47	4.5	0.23	2.9	4.7	0.21	5	4.0
STD DS7	Standard	0.087	13	221	1.17	405	0.132	51	1.11	0.103	0.50	4.6	0.25	2.6	4.7	0.20	5	3.4
STD DS7 Expected		0.08	12.7	163	1.05	370.3	0.124	38.6	0.959	0.073	0.44	3.8	0.2	2.5	4.19	0.21	4.6	3.5
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5

QUALITY CONTROL REPORT

SMI08000468.1

		WGHT	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15
		Wgt	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
Prep Wash																					
G1	Prep Blank	<0.01	1.1	2.3	4.2	47	<0.1	4.8	4.1	518	1.73	<0.5	2.5	<0.5	4.0	45	<0.1	<0.1	<0.1	34	0.44

QUALITY CONTROL REPORT

SMI08000468.1

		1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm
		0.001	1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5
Prep Wash																		
G1	Prep Blank	0.076	6	9	0.55	210	0.103	<1	0.92	0.065	0.48	0.3	<0.01	1.6	0.4	<0.05	5	<0.5





ACME ANALYTICAL LABORATORIES LTD.  
852 E. Hastings St. Vancouver BC V6A 1R6 Canada  
Phone (604) 253-3158 Fax (604) 253-1716

[www.acmelab.com](http://www.acmelab.com)

**Client:** Cadillac Mining Exploration

3741 W. 36th Ave  
Vancouver BC V6N 2S3 Canada

Submitted By: Victor Erickson

Receiving Lab: Acme Analytical Laboratories (Vancouver) Ltd.

Received: January 03, 2008

Report Date: February 13, 2008

Page: 1 of 3

## CERTIFICATE OF ANALYSIS

SMI08000470.1

### CLIENT JOB INFORMATION

Project: None Given  
Shipment ID:  
P.O. Number ACME FILE: A818001  
Number of Samples: 37

### SAMPLE DISPOSAL

### SAMPLE PREPARATION AND ANALYTICAL PROCEDURES


Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	37	Split and Crush to 70% passing 10 mesh		
1DX	37	1:1:1 Aqua Regia digestion ICP-MS analysis	15	Completed

### ADDITIONAL COMMENTS

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Cadillac Mining Exploration  
3741 W. 36th Ave  
Vancouver BC V6N 2S3  
Canada

CC: Andre Audet



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



ACME ANALYTICAL LABORATORIES LTD.

852 E. Hastings St. Vancouver BC V6A 1R6 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client:

**Cadillac Mining Exploration**

3741 W. 36th Ave  
Vancouver BC V6N 2S3 Canada

Project:

None Given

Report Date:

February 13, 2008

Page:

2 of 3

Part 1

# CERTIFICATE OF ANALYSIS

**SMI08000470.1**

Method Analyte Unit MDL	WGHT	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15
	Wgt	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
	0.01	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
774893	Drill Core	4.6	0.8	17.0	23.7	90	<0.1	38.7	11.3	477	3.18	57.7	0.3	2.2	1.2	287	0.5	0.9	<0.1	18	13.99
774894	Drill Core	4.4	0.7	22.6	22.6	73	<0.1	58.8	22.3	448	3.99	86.0	0.3	2.2	1.1	198	0.3	0.7	<0.1	20	8.27
774895	Drill Core	1.8	0.9	59.4	14.1	49	0.1	55.5	27.0	756	3.92	75.2	0.2	1.7	1.3	168	0.2	2.6	<0.1	30	9.99
774896	Drill Core	1.4	0.5	45.5	10.4	67	<0.1	89.2	31.7	642	4.96	31.2	0.1	1.2	1.4	170	<0.1	1.1	<0.1	37	6.98
774897	Drill Core	2.8	0.1	12.2	14.5	80	<0.1	99.4	36.8	677	6.80	21.0	0.1	3.0	1.7	192	<0.1	0.1	<0.1	39	5.67
774898	Drill Core	1.6	0.9	48.9	8.7	60	0.1	91.0	39.9	238	5.22	128.0	0.1	1.6	0.5	185	<0.1	0.5	<0.1	30	1.14
774899	Drill Core	1.8	<0.1	10.1	11.4	89	<0.1	92.6	33.8	749	6.27	19.1	0.1	0.8	1.5	178	0.1	0.2	<0.1	33	5.30
774900	Drill Core	0.7	0.2	4.3	1.3	14	<0.1	1.9	1.0	230	0.46	0.8	0.8	2.0	<0.1	48	<0.1	<0.1	<0.1	<2	22.56
774901	Drill Core	1.4	0.2	9.1	10.9	54	<0.1	64.9	21.2	330	4.36	23.9	0.2	2.5	1.2	158	0.1	0.2	<0.1	30	2.44
774902	Drill Core	1.5	4.3	129.4	14.4	74	0.2	106.3	58.6	514	4.85	194.0	0.2	0.8	0.9	167	0.2	2.7	<0.1	36	4.55
774903	Drill Core	1.1	0.1	15.9	13.0	78	<0.1	66.0	16.4	896	5.90	32.6	0.2	2.2	1.0	177	0.2	0.3	<0.1	34	6.82
774904	Drill Core	4.6	0.5	29.5	10.6	67	<0.1	74.7	22.1	696	4.60	78.1	0.2	2.4	1.1	178	0.1	0.4	<0.1	34	6.37
774905	Drill Core	1.9	0.3	26.5	14.6	63	<0.1	69.8	21.6	706	4.25	50.3	0.7	1.2	1.1	175	0.2	0.5	<0.1	39	7.26
774906	Drill Core	4.6	0.1	22.6	25.1	58	<0.1	53.5	17.2	662	3.80	21.4	0.4	0.7	1.1	196	0.2	0.6	<0.1	43	6.08
774907	Drill Core	1.5	0.2	42.3	5.0	68	<0.1	60.3	27.3	598	4.07	5.1	0.3	0.7	1.5	116	0.3	0.2	<0.1	66	4.90
774908	Drill Core	2.3	0.3	11.8	18.9	32	<0.1	31.6	13.7	194	4.97	5.1	0.4	1.4	1.1	154	<0.1	1.8	<0.1	35	0.61
774909	Drill Core	2.3	0.2	9.6	15.9	39	<0.1	32.2	13.6	232	3.86	5.3	0.4	1.2	1.6	155	<0.1	1.4	<0.1	46	1.09
774910	Drill Core	4.6	0.3	6.9	8.6	80	<0.1	51.8	23.0	966	4.14	4.3	0.2	0.9	1.2	132	0.3	0.6	<0.1	83	5.35
RRE 774910	Drill Core		0.3	6.1	8.4	74	<0.1	49.3	24.7	965	4.16	4.5	0.2	0.7	1.2	133	0.4	0.6	<0.1	82	5.42
774911	Drill Core	1.5	0.2	6.5	15.0	186	<0.1	49.7	19.9	891	3.91	4.3	0.3	2.2	1.4	118	1.1	1.5	<0.1	73	4.23
774912	Drill Core	7.6	1.2	187.1	19.7	558	6.5	50.4	20.5	1994	3.64	46.3	0.1	1.0	0.6	141	4.7	88.0	<0.1	51	6.88
774913	Drill Core	0.6	0.2	17.9	16.8	170	0.2	54.8	16.9	520	3.90	3.5	<0.1	0.7	1.1	106	0.9	2.9	<0.1	33	3.62
774914	Drill Core	4.5	0.1	6.8	14.6	269	0.2	44.4	16.8	868	2.95	3.6	0.2	1.4	1.1	137	1.7	1.8	<0.1	64	4.43
774915	Drill Core	2	0.1	23.2	11.2	203	0.6	62.5	19.4	819	2.72	4.4	0.1	2.0	1.3	124	1.0	1.4	<0.1	77	5.07
774916	Drill Core	0.15	0.2	6.5	10.6	177	<0.1	49.3	20.9	925	4.20	2.8	0.1	1.4	1.2	92	1.0	1.9	<0.1	58	5.89
774917	Drill Core	0.6	0.2	46.5	16.9	424	2.1	45.5	19.0	909	3.38	8.1	<0.1	1.7	0.7	142	3.1	9.2	<0.1	47	5.36
774918	Drill Core	1.7	0.2	6.1	14.2	225	<0.1	48.3	21.3	844	3.78	4.6	0.2	1.4	1.3	94	1.1	2.6	<0.1	69	5.51
774919	Drill Core	1.6	0.3	5.1	20.3	204	<0.1	46.6	20.4	682	3.67	5.9	0.3	1.4	1.4	107	1.0	3.2	<0.1	84	5.13
774920	Drill Core	0.8	<0.1	0.7	1.0	15	<0.1	2.0	0.8	202	0.36	0.5	1.0	2.9	0.1	48	<0.1	<0.1	<0.1	3	22.39
774921	Drill Core	1	0.3	10.7	23.0	165	<0.1	57.0	26.7	612	4.25	6.9	0.2	0.7	1.3	132	0.7	3.0	<0.1	77	4.62



ACME ANALYTICAL LABORATORIES LTD.  
 852 E. Hastings St. Vancouver BC V6A 1R6 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Cadillac Mining Exploration

3741 W. 36th Ave  
 Vancouver BC V6N 2S3 Canada

Project: None Given

Report Date: February 13, 2008

Page: 2 of 3 Part 2

# CERTIFICATE OF ANALYSIS

SMI08000470.1

Method Analyte Unit MDL	1DX15 P % 0.001	1DX15 La ppm 1	1DX15 Cr ppm 1	1DX15 Mg % 0.01	1DX15 Ba ppm 1	1DX15 Ti % 0.001	1DX15 B ppm 1	1DX15 Al % 0.01	1DX15 Na % 0.001	1DX15 K % 0.01	1DX15 W ppm 0.1	1DX15 Hg ppm 0.01	1DX15 Sc ppm 0.1	1DX15 Ti ppm 0.1	1DX15 S % 0.05	1DX15 Ga ppm 1	1DX15 Se ppm 0.5	
774893	Drill Core	0.113	13	15	0.79	95	<0.001	5	0.52	0.180	0.18	<0.1	0.04	8.0	0.1	0.49	<1	0.7
774894	Drill Core	0.171	11	15	0.74	98	0.002	6	0.63	0.230	0.21	<0.1	0.07	9.2	0.2	0.59	1	0.9
774895	Drill Core	0.126	11	22	0.59	115	0.002	4	0.59	0.243	0.21	<0.1	0.02	9.7	<0.1	0.17	<1	0.8
774896	Drill Core	0.097	8	23	0.70	213	0.001	6	0.59	0.248	0.19	<0.1	0.02	10.2	<0.1	0.13	<1	0.7
774897	Drill Core	0.124	8	32	0.83	746	0.002	6	0.72	0.324	0.24	<0.1	<0.01	11.7	<0.1	<0.05	<1	0.9
774898	Drill Core	0.042	2	15	0.57	152	<0.001	5	0.72	0.442	0.20	<0.1	0.04	15.1	<0.1	0.44	<1	0.6
774899	Drill Core	0.075	8	22	0.88	341	<0.001	7	0.65	0.288	0.24	<0.1	0.04	11.3	<0.1	<0.05	1	0.9
774900	Drill Core	0.017	<1	<1	13.49	8	<0.001	<1	0.04	0.004	0.02	<0.1	<0.01	0.3	<0.1	<0.05	<1	0.8
774901	Drill Core	0.062	6	18	0.74	162	0.001	6	0.70	0.349	0.24	<0.1	<0.01	11.9	<0.1	<0.05	<1	0.6
774902	Drill Core	0.050	7	28	0.94	128	<0.001	5	0.62	0.291	0.19	<0.1	0.05	12.5	0.2	0.25	<1	0.8
774903	Drill Core	0.083	8	27	1.12	143	0.002	5	0.63	0.277	0.20	<0.1	0.01	11.0	<0.1	<0.05	<1	<0.5
774904	Drill Core	0.065	7	25	1.06	112	0.002	5	0.65	0.286	0.19	<0.1	0.02	12.3	0.3	0.11	<1	0.7
774905	Drill Core	0.064	8	32	1.29	93	<0.001	5	0.64	0.245	0.20	<0.1	0.01	12.0	0.2	0.08	1	0.5
774906	Drill Core	0.047	8	24	1.06	1911	<0.001	4	0.59	0.253	0.24	<0.1	0.03	11.4	0.1	0.06	<1	0.9
774907	Drill Core	0.109	12	25	1.17	420	0.002	4	0.63	0.215	0.23	<0.1	<0.01	10.4	<0.1	<0.05	1	<0.5
774908	Drill Core	0.004	3	42	0.28	240	0.009	6	0.66	0.397	0.24	<0.1	<0.01	9.1	<0.1	<0.05	<1	<0.5
774909	Drill Core	0.076	11	33	0.38	187	0.006	7	0.81	0.368	0.31	<0.1	<0.01	9.9	0.1	<0.05	1	<0.5
774910	Drill Core	0.095	9	36	2.07	415	0.021	4	0.44	0.126	0.15	<0.1	<0.01	10.4	<0.1	<0.05	1	<0.5
RRE 774910	Drill Core	0.101	10	35	2.11	530	0.021	5	0.41	0.126	0.15	0.1	<0.01	9.6	<0.1	<0.05	1	<0.5
774911	Drill Core	0.100	9	38	1.52	299	0.006	8	0.68	0.201	0.29	<0.1	<0.01	11.2	<0.1	<0.05	1	<0.5
774912	Drill Core	0.069	3	13	2.32	2592	0.002	6	0.32	0.044	0.16	<0.1	0.12	6.9	<0.1	0.08	<1	0.6
774913	Drill Core	0.069	8	18	1.27	744	0.005	11	0.70	0.165	0.34	<0.1	0.01	9.9	0.2	<0.05	1	<0.5
774914	Drill Core	0.096	6	23	1.48	1807	0.003	9	0.70	0.109	0.30	<0.1	0.02	10.1	0.1	<0.05	1	0.7
774915	Drill Core	0.125	10	17	1.47	1657	0.003	9	0.74	0.123	0.33	<0.1	0.05	12.4	0.1	<0.05	1	0.5
774916	Drill Core	0.099	8	40	2.23	413	0.023	8	0.42	0.090	0.20	0.1	<0.01	11.8	<0.1	<0.05	1	<0.5
774917	Drill Core	0.053	5	17	1.76	1963	0.002	8	0.52	0.092	0.25	<0.1	0.25	9.7	0.1	<0.05	<1	<0.5
774918	Drill Core	0.120	9	32	1.99	233	0.011	10	0.57	0.095	0.27	<0.1	<0.01	12.3	<0.1	<0.05	1	0.7
774919	Drill Core	0.121	10	32	2.12	231	0.007	10	0.62	0.121	0.27	0.1	<0.01	11.8	<0.1	<0.05	1	0.5
774920	Drill Core	0.029	<1	1	13.22	20	0.002	<1	0.07	0.002	0.04	<0.1	<0.01	0.3	<0.1	<0.05	<1	<0.5
774921	Drill Core	0.107	10	32	2.45	76	0.013	8	0.62	0.138	0.24	0.1	<0.01	9.9	<0.1	<0.05	1	<0.5



ACME ANALYTICAL LABORATORIES LTD.  
 852 E. Hastings St. Vancouver BC V6A 1R6 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Cadillac Mining Exploration**

3741 W. 36th Ave  
 Vancouver BC V6N 2S3 Canada

Project: None Given

Report Date: February 13, 2008

Page: 3 of 3 Part 1

# CERTIFICATE OF ANALYSIS

SMI08000470.1

Method	WGHT	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15
Analyte	Wgt	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
774922	Drill Core	1.5	0.2	11.6	18.1	137	<0.1	46.5	21.0	548	3.64	5.7	0.1	1.3	1.0	137	0.9	2.1	<0.1	84	5.16
774923	Drill Core	1.6	0.2	9.0	16.7	276	<0.1	65.2	27.8	1519	4.22	5.6	0.2	1.8	1.2	146	1.2	1.9	<0.1	65	7.81
774924	Drill Core	0.9	0.3	3.3	14.4	276	<0.1	48.4	24.7	1403	3.45	3.2	0.2	0.9	0.8	227	1.6	1.4	<0.1	65	7.81
774925	Drill Core	1.8	0.3	4.2	14.5	165	<0.1	49.1	21.2	931	3.22	6.2	0.2	1.8	1.1	121	0.8	1.7	<0.1	65	5.60
774926	Drill Core	1.6	0.3	3.9	9.8	72	<0.1	37.8	20.3	883	3.81	4.6	0.3	1.5	1.2	119	0.6	1.1	<0.1	73	6.15
774927	Drill Core	0.9	0.3	18.0	10.9	58	<0.1	39.8	16.7	684	3.26	4.4	0.2	1.3	1.1	106	0.3	0.9	<0.1	83	4.43
774928	Drill Core	4.5	0.3	9.4	13.4	82	<0.1	41.1	19.4	874	3.83	4.9	0.3	<0.5	1.2	118	0.5	1.4	<0.1	76	5.50



ACME ANALYTICAL LABORATORIES LTD.  
 852 E. Hastings St. Vancouver BC V6A 1R6 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Cadillac Mining Exploration

3741 W. 36th Ave  
 Vancouver BC V6N 2S3 Canada

Project: None Given

Report Date: February 13, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000470.1

Method	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	
774922	Drill Core	0.103	9	32	2.27	66	0.011	7	0.54	0.125	0.18	<0.1	<0.01	9.1	<0.1	<0.05	1	0.8
774923	Drill Core	0.124	8	30	3.24	724	0.018	11	0.58	0.110	0.23	<0.1	0.02	9.7	<0.1	<0.05	1	<0.5
774924	Drill Core	0.104	6	20	3.04	2588	0.004	6	0.41	0.086	0.15	<0.1	<0.01	7.6	0.2	0.07	<1	<0.5
774925	Drill Core	0.130	9	24	2.10	537	0.005	8	0.60	0.123	0.22	0.1	0.02	10.3	0.1	<0.05	1	<0.5
774926	Drill Core	0.122	11	23	2.39	336	0.007	7	0.76	0.129	0.21	0.1	<0.01	9.7	<0.1	<0.05	1	<0.5
774927	Drill Core	0.115	10	32	1.81	241	0.017	6	0.65	0.099	0.13	0.1	0.01	9.0	<0.1	<0.05	2	<0.5
774928	Drill Core	0.120	10	27	2.12	78	0.013	7	0.67	0.124	0.18	0.1	<0.01	10.9	<0.1	<0.05	1	<0.5

## QUALITY CONTROL REPORT

SMI08000470.1

Method	WGHT	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	
Analyte	Wgt	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
774905	Drill Core	1.9	0.3	26.5	14.6	63	<0.1	69.8	21.6	706	4.25	50.3	0.7	1.2	1.1	175	0.2	0.5	<0.1	39	7.26
REP 774905	QC		0.3	28.9	14.6	61	0.1	73.9	22.7	745	4.36	50.4	0.7	1.2	1.2	182	0.3	0.5	<0.1	41	7.39
Reference Materials																					
STD DS7	Standard		19.1	101.4	69.8	410	0.8	56.5	9.2	604	2.33	50.6	4.8	65.7	4.5	76	6.2	6.3	4.5	81	0.98
STD DS7	Standard		19.0	95.6	64.9	391	0.8	53.9	8.6	631	2.26	49.6	4.9	62.9	4.5	79	6.1	6.2	4.5	86	0.98
STD DS7	Standard		17.8	94.8	64.9	392	0.8	52.1	9.0	597	2.35	49.5	4.7	66.5	4.1	73	5.8	5.9	4.2	80	0.92
STD DS7	Standard		19.6	94.4	64.2	369	0.8	51.5	8.7	609	2.27	48.9	4.6	191.4	4.5	75	5.7	5.9	4.1	74	0.92
STD DS7 Expected			20.92	109	70.6	411	0.89	56	9.7	627	2.39	48.2	4.9	70	4.4	68.7	6.38	5.86	4.51	86	0.93
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
Prep Wash																					
G1	Prep Blank	<0.01	0.8	3.9	2.8	44	<0.1	7.0	4.3	527	1.80	<0.5	2.5	3.0	4.3	55	<0.1	0.2	<0.1	34	0.47

**QUALITY CONTROL REPORT**

**SMI08000470.1**

Method		1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15	1DX15
Analyte		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm
MDL		0.001	1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.01	0.01	0.1	0.1	0.05	1	0.5
Pulp Duplicates																		
774905	Drill Core	0.064	8	32	1.29	93	<0.001	5	0.64	0.245	0.20	<0.1	0.01	12.0	0.2	0.08	1	0.5
REP 774905	QC	0.065	9	34	1.34	96	<0.001	4	0.64	0.260	0.20	<0.1	0.03	12.8	0.2	0.08	1	0.7
Reference Materials																		
STD DS7	Standard	0.085	13	180	1.05	378	0.121	43	1.02	0.101	0.47	4.0	0.20	2.5	4.4	0.19	5	4.1
STD DS7	Standard	0.079	14	192	1.01	383	0.123	39	1.04	0.102	0.44	3.9	0.19	2.7	4.1	0.19	5	3.9
STD DS7	Standard	0.077	12	178	1.01	354	0.116	39	1.00	0.092	0.42	3.7	0.21	2.4	4.1	0.19	4	4.0
STD DS7	Standard	0.075	13	177	0.97	357	0.120	41	0.99	0.095	0.44	3.7	0.18	2.4	3.9	0.19	5	3.8
STD DS7 Expected		0.08	12.7	163	1.05	370.3	0.124	38.6	0.959	0.073	0.44	3.8	0.2	2.5	4.19	0.21	4.6	3.5
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5
Prep Wash																		
G1	Prep Blank	0.072	7	11	0.59	208	0.115	1	1.00	0.073	0.49	0.3	<0.01	2.0	0.3	<0.05	5	<0.5

## **Bibliography**

Aziz, M. L.; Dec 1990; Induced Polarization Geophysics on the Eric Property Mineral Claims.

Carter, N.C. Jan 2003; Silver Streak Property; letter report



## Statement of Qualifications

I, Andre J. Audet of Courtenay British Columbia do hereby certify that:

I am a graduate of the University of British Columbia, British Columbia and hold a Bachelor of Applied Science degree in Geological Sciences.

I am a member of the Association of Professional Engineers and Geoscientists of British Columbia.

I have practiced professionally in geology and mining since 1972.

I am a consulting Geological Engineer.

I have authored this report

Courtenay, British Columbia; July 21, 2008

Respectfully Submitted:



Andre J. Audet P.Eng

