


BC Geological Survey
Assessment Report
30144 (I)

APPENDIX B – ASSAY CERTIFICATES
PART 3

Volume 8 of 8



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2135

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

13-Feb-08


Attention: Bob Singh

No. of samples received: 63
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-126
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-04819	0.08	0.002
2	S07-04820	<0.03	<0.001
3	S07-04821	<0.03	<0.001
4	S07-04822	<0.03	<0.001
5	S07-04823	0.03	0.001
6	S07-04824	0.04	0.001
7	S07-04825	<0.03	<0.001
8	S07-04826	<0.03	<0.001
9	S07-04827	0.06	0.002
10	S07-04828	<0.03	<0.001
11	S07-04829	<0.03	<0.001
12	S07-04830	0.03	0.001
13	S07-04831	0.03	0.001
14	S07-04832	0.03	0.001
15	S07-04833	0.07	0.002
16	S07-04834	0.08	0.002
17	S07-04835	0.08	0.002
18	S07-04836	0.09	0.003
19	S07-04837	0.10	0.003
20	S07-04838	0.13	0.004
21	S07-04839	1.45	0.042
22	S07-04840	0.35	0.010
23	S07-04841	0.17	0.005
24	S07-04842	0.20	0.006
25	S07-04843	0.09	0.003
26	S07-04844	0.29	0.009
27	S07-04845	0.21	0.006
28	S07-04846	0.07	0.002
29	S07-04847	0.29	0.008

* = 30g FA


ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #		Au (g/t)	Au (oz/t)
30	S07-04848	*	<0.03	<0.001
31	S07-04849		0.19	0.005
32	S07-04850		0.03	0.001
33	S07-04851		0.23	0.007
34	S07-04852		<0.03	<0.001
35	S07-04853		0.38	0.011
36	S07-04854		0.20	0.006
37	S07-04855		0.64	0.019
38	S07-04856		0.22	0.006
39	S07-04857		0.16	0.005
40	S07-04858	*	0.42	0.012
41	S07-04859		0.33	0.010
42	S07-04860		0.84	0.024
43	S07-04861		2.45	0.072
44	S07-04862		0.51	0.015
45	S07-04863		1.81	0.053
46	S07-04864		5.17	0.151
47	S07-04865		1.90	0.055
48	S07-04866		2.32	0.068
49	S07-04867		0.76	0.022
50	S07-04868		<0.03	<0.001
51	S07-04869		<0.03	<0.001
52	S07-04870		0.34	0.010
53	S07-04871		0.66	0.019
54	S07-04872		0.54	0.016
55	S07-04873		0.36	0.011
56	S07-04874		0.32	0.009
57	S07-04875		0.07	0.002
58	S07-04876		0.43	0.012
59	S07-04877		0.27	0.008
60	S07-04878		0.08	0.002
61	S07-04879		0.05	0.002
62	S07-04880	*	<0.03	<0.001
63	S07-04881		0.25	0.007

QC DATA:**Resplit:**

1	S07-04819	0.07	0.002
36	S07-04854	0.21	0.006

Standard:

OXi54	1.86	0.054
OXi54	1.90	0.055
OXi54	1.86	0.054
OXi54	1.88	0.055
OXi54	1.87	0.055

* = 30g FA

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

JJ/sa
XLS/07

Jutta Jealouse
ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS 2007- 2135

Skygold Ventures
615 - 800 W. Pender Street
Vancouver, BC
V6B 2V6

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 63
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-126
Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Tl%	U	V	W	Y	Zn
1	S07-04819	1.0	5.16	375	995	<5	4.46	1	31	645	81	5.29	1.22	20	2.37	1222	16	0.18	264	810	38	10	<20	272	0.07	<10	221	<10	8	178
2	S07-04820	0.8	5.66	230	240	<5	3.51	<1	41	854	88	5.56	1.19	<10	5.76	1339	<1	0.58	290	610	22	10	<20	174	0.07	<10	135	<10	6	125
3	S07-04821	1.3	5.18	120	495	<5	3.29	<1	25	389	26	3.69	1.21	10	3.89	1106	<1	0.37	115	500	14	5	<20	181	0.08	<10	100	<10	7	55
4	S07-04822	1.2	5.35	70	545	<5	2.68	<1	20	471	94	3.60	1.24	10	3.07	849	<1	0.29	82	470	14	5	<20	131	0.09	<10	80	<10	8	38
5	S07-04823	1.3	6.51	95	535	<5	2.41	<1	18	269	109	3.68	1.29	<10	1.74	844	<1	0.47	83	540	16	<5	<20	135	0.10	<10	78	<10	8	65
6	S07-04824	0.8	6.33	140	390	<5	4.17	<1	31	467	178	5.15	1.30	<10	2.36	1428	<1	0.63	119	710	22	5	<20	182	0.08	<10	150	<10	7	112
7	S07-04825	4.3	6.85	85	660	<5	4.21	<1	25	427	45	4.33	1.34	10	4.17	1464	<1	0.57	84	710	16	<5	<20	208	0.11	<10	147	<10	9	71
8	S07-04826	1.4	5.22	130	200	<5	5.25	<1	42	698	80	6.57	1.44	<10	6.11	2855	<1	0.41	193	680	16	5	<20	191	0.07	<10	226	<10	6	145
9	S07-04827	2.6	4.98	90	625	<5	1.19	<1	24	565	124	4.50	1.36	20	1.87	1184	<1	0.15	100	380	16	10	<20	85	0.10	<10	99	<10	6	98
10	S07-04828	3.3	5.39	90	805	<5	1.38	<1	24	518	129	4.61	1.35	20	2.03	1279	<1	0.16	99	440	22	10	<20	94	0.11	<10	104	<10	7	103
11	S07-04829	0.2	1.82	95	25	<5	>10	<1	<1	5	10	0.57	0.09	<10	>10	242	<1	2.50	4	170	14	<5	<20	62	<0.01	<10	3	<10	3	18
12	S07-04830	2.4	6.49	85	350	<5	3.38	3	26	533	185	6.91	2.22	20	1.32	1084	48	0.15	126	890	38	15	<20	116	0.12	<10	309	<10	9	218
13	S07-04831	2.2	5.41	50	270	<5	2.35	2	22	473	171	5.68	2.26	20	1.27	938	36	0.14	96	730	34	10	<20	111	0.10	<10	273	<10	9	172
14	S07-04832	2.8	5.07	50	285	<5	2.77	1	23	458	153	4.35	2.47	20	2.02	1279	21	0.17	94	640	24	10	<20	165	0.10	<10	270	<10	11	123
15	S07-04833	1.4	4.88	25	175	<5	2.66	3	19	411	145	4.47	2.31	20	1.68	1015	40	0.12	73	760	24	10	<20	164	0.10	<10	288	<10	9	194
16	S07-04834	2.0	5.19	30	230	<5	2.83	2	23	583	139	5.29	2.07	20	1.98	1179	35	0.12	105	850	28	10	<20	154	0.10	<10	273	<10	10	196
17	S07-04835	2.4	4.93	25	200	<5	2.60	3	20	489	120	4.63	2.35	20	1.49	1015	33	0.12	73	920	32	10	<20	153	0.11	<10	284	<10	10	247
18	S07-04836	2.8	4.56	30	210	<5	3.83	3	20	374	81	4.68	2.29	20	2.06	1293	40	0.15	82	830	38	10	<20	217	0.08	<10	262	<10	9	278
19	S07-04837	1.6	5.24	35	210	<5	3.41	2	20	394	65	5.09	2.22	20	1.67	1218	35	0.12	79	820	36	10	<20	175	0.11	<10	239	<10	8	188
20	S07-04838	1.4	4.41	25	180	<5	3.07	2	16	402	57	4.20	2.21	10	1.73	1135	27	0.09	65	720	32	10	<20	186	0.09	<10	230	<10	7	188
21	S07-04839	2.8	5.29	45	185	<5	4.07	<1	25	573	73	4.78	2.38	20	2.01	1244	30	0.16	116	640	42	10	<20	217	0.10	<10	220	<10	11	96
22	S07-04840	2.2	5.15	35	280	<5	3.62	2	24	526	70	4.96	2.45	20	1.76	1184	33	0.11	96	900	44	15	<20	196	0.11	<10	237	<10	9	175
23	S07-04841	1.6	5.43	30	220	<5	3.97	2	22	549	58	5.10	2.17	20	1.78	1279	38	0.14	91	940	38	15	<20	192	0.11	<10	240	<10	9	216
24	S07-04842	2.2	4.28	20	115	<5	2.61	3	17	520	94	4.35	2.10	20	1.25	903	34	0.07	61	840	40	10	<20	136	0.10	<10	229	<10	9	173
25	S07-04843	1.4	6.08	35	85	<5	2.48	2	19	347	50	4.14	2.32	20	1.19	802	26	0.13	54	1340	34	10	<20	128	0.15	<10	232	<10	10	186

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn	
26	S07-04844	0.8	7.59	50	160	<5	3.59	1	14	262	81	3.03	1.29	20	1.65	791	4	0.85	23	860	16	<5	<20	164	0.16	<10	148	<10	11	115
27	S07-04845	0.7	6.78	20	380	<5	3.02	<1	9	215	105	3.11	1.22	10	1.82	791	2	1.01	19	640	16	<5	<20	163	0.14	<10	124	<10	10	122
28	S07-04846	0.4	7.31	30	600	<5	4.10	<1	9	164	66	3.24	1.36	10	2.27	1195	2	0.98	20	700	16	<5	<20	276	0.15	<10	137	<10	12	103
29	S07-04847	0.6	6.19	35	200	<5	3.79	<1	12	298	75	3.08	0.99	20	1.78	1219	4	0.56	23	680	14	<5	<20	220	0.12	<10	130	<10	10	59
30	S07-04848	0.2	0.90	5	100	<5	>10	<1	<1	4	3	0.59	0.13	<10	>10	240	<1	0.09	3	170	<2	<5	<20	58	<0.01	<10	3	<10	1	17
31	S07-04849	0.8	5.78	30	285	<5	4.66	<1	8	330	74	3.11	1.79	10	2.04	1325	4	0.23	18	520	18	<5	<20	282	0.10	<10	120	<10	11	65
32	S07-04850	0.4	6.16	55	150	<5	2.81	1	12	297	68	3.00	1.29	20	1.50	856	5	0.41	25	510	16	<5	<20	129	0.13	<10	153	<10	8	138
33	S07-04851	0.5	5.53	25	140	<5	2.72	1	14	317	65	3.20	1.12	10	1.39	819	5	0.73	31	450	12	<5	<20	138	0.13	<10	146	<10	7	104
34	S07-04852	0.4	5.77	15	1270	<5	1.93	<1	8	254	35	2.33	1.16	10	1.50	565	4	0.45	18	370	12	<5	<20	108	0.12	<10	105	<10	6	114
35	S07-04853	0.6	7.17	30	245	<5	3.28	<1	12	334	198	3.68	1.68	20	2.12	1120	5	0.89	25	750	20	5	<20	212	0.16	<10	154	<10	8	89
36	S07-04854	0.5	6.87	15	715	<5	1.77	<1	13	203	80	3.67	1.59	10	1.83	737	2	0.76	20	530	20	<5	<20	118	0.16	<10	141	<10	6	87
37	S07-04855	0.6	6.70	15	250	<5	2.05	1	13	321	133	3.57	1.63	20	1.73	863	3	0.57	23	540	26	<5	<20	143	0.15	<10	143	<10	8	154
38	S07-04856	0.8	7.39	15	1565	<5	2.13	<1	9	272	143	3.12	1.51	20	1.85	1016	3	0.65	21	530	20	<5	<20	140	0.17	<10	158	<10	9	109
39	S07-04857	0.4	6.13	15	1510	<5	2.06	<1	5	411	44	1.89	1.57	10	1.20	706	3	0.40	15	420	14	5	<20	140	0.14	<10	105	<10	8	67
40	S07-04858	0.9	5.46	130	320	<5	0.22	<1	8	28	36	3.63	4.49	<10	0.28	167	4	0.10	15	430	10	45	<20	41	0.39	<10	70	<10	11	50
41	S07-04859	0.6	5.74	30	375	<5	2.56	<1	12	416	156	3.87	1.50	20	1.73	898	4	0.50	27	640	16	<5	<20	160	0.13	<10	132	<10	10	120
42	S07-04860	0.8	7.40	20	195	<5	3.62	<1	19	285	194	4.66	1.51	20	2.12	1462	<1	0.98	38	730	18	5	<20	223	0.17	<10	169	<10	9	83
43	S07-04861	1.2	5.79	30	105	<5	2.67	<1	19	272	167	4.25	1.71	20	1.25	743	<1	1.04	38	790	20	<5	<20	164	0.16	<10	115	<10	9	76
44	S07-04862	1.0	7.46	55	225	<5	4.31	2	17	244	235	4.23	1.86	20	1.90	1024	17	0.86	37	860	18	<5	<20	195	0.18	<10	287	<10	7	240
45	S07-04863	0.8	6.16	25	70	<5	2.81	3	19	202	152	4.61	2.10	20	1.37	631	32	0.64	43	980	24	<5	<20	128	0.16	<10	372	<10	7	309
46	S07-04864	1.6	7.09	30	80	<5	3.01	2	16	307	199	5.14	2.02	20	1.48	781	56	0.68	52	740	20	5	<20	126	0.17	<10	366	<10	7	220
47	S07-04865	0.9	6.12	15	120	<5	3.29	23	14	283	251	3.98	1.58	20	1.46	791	20	0.40	39	790	20	<5	<20	147	0.19	<10	277	<10	7	1637
48	S07-04866	1.4	6.71	25	310	<5	3.83	3	21	293	98	5.09	2.51	20	1.63	915	25	0.49	46	850	24	<5	<20	176	0.16	<10	231	<10	10	236
49	S07-04867	0.5	6.42	20	195	<5	2.52	<1	11	312	69	2.89	1.55	20	1.24	548	9	0.84	24	490	16	<5	<20	126	0.15	<10	126	<10	7	85
50	S07-04868	0.2	6.45	15	840	<5	2.19	<1	8	141	37	2.41	1.82	20	1.53	589	<1	1.08	17	410	16	<5	<20	146	0.16	<10	77	<10	8	95
51	S07-04869	0.4	6.44	15	835	<5	2.32	<1	9	87	38	2.33	1.84	20	1.53	615	<1	1.06	15	390	16	<5	<20	155	0.15	<10	74	<10	9	85
52	S07-04870	1.4	7.79	30	265	<5	3.97	<1	20	235	92	5.68	1.94	10	2.40	1121	5	0.70	26	910	26	<5	<20	203	0.18	<10	193	<10	8	89
53	S07-04871	1.0	6.13	45	370	<5	3.55	<1	25	245	62	5.40	2.21	10	1.59	943	11	0.93	34	750	16	<5	<20	148	0.15	<10	153	<10	9	46
54	S07-04872	0.4	6.80	20	185	<5	2.85	<1	9	151	77	2.68	1.54	20	1.38	666	3	0.77	16	600	14	<5	<20	133	0.16	<10	113	<10	10	52
55	S07-04873	0.2	6.31	20	375	<5	3.45	<1	6	175	36	2.60	1.51	20	1.35	814	4	1.21	10	740	14	<5	<20	141	0.14	<10	71	<10	9	65
56	S07-04874	1.0	6.67	25	75	<5	2.39	<1	12	152	69	3.62	2.48	10	0.96	583	6	1.05	15	500	18	<5	<20	111	0.14	<10	77	<10	8	62
57	S07-04875	0.4	6.91	15	1270	<5	2.64	<1	8	149	44	2.66	1.71	10	1.20	707	<1	0.94	13	420	20	<5	<20	129	0.16	<10	84	<10	8	68
58	S07-04876	0.5	6.60	25	215	<5	2.70	<1	9	131	59	3.21	2.36	20	1.34	768	2	0.48	11	790	18	<5	<20	160	0.17	<10	124	<10	9	85
59	S07-04877	1.4	7.06	25	605	<5	4.67	<1	14	177	102	4.42	1.86	20	1.78	1676	1	0.54	17	1120	30	<5	<20	239	0.21	<10	124	<10	12	92
60	S07-04878	0.3	6.91	25	600	<5	3.88	<1	17	155	62	5.15	1.82	20	1.62	1443	<1	0.73	15	1070	16	<5	<20	173	0.21	<10	104	<10	9	90
61	S07-04879	0.6	6.76	35	565	<5	5.79	<1	19	125	32	4.96	1.73	10	1.64	1836	<1	1.99	16	770	14	<5	<20	244	0.16	<10	146	<10	6	90
62	S07-04880	<0.2	0.68	5	70	<5	>10	<1	<1	10	2	0.57	0.10	<10	>10	237	<1	0.05	3	160	4	<5	<20	49	<0.01	<10	3	<10	1	11
63	S07-04881	0.8	6.57	25	205	<5	2.94	<1	18	409	76	4.94	1.33	20	0.99	831	15	1.31	28	700	18	<5	<20	157	0.23	<10	112	<10	8	87

QC DATA:


Repeat:


1	S07-04819	0.8	5.07	365	985	<5	4.32	1	31	628	80	5.19	1.28	20	2.40	1184	15	0.18	253	790	36	10	<20	271	0.06	<10	213	<10	8	169
10	S07-04828	3.3	5.70	100	790	<5	1.44	<1	25	532	130	4.93	1.48	20	2.11	1307	<1	0.18	105	470	24	10	<20	98	0.11	<10	105	<10	7	105

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
Repeats Continued:																														
19	S07-04837	1.8	5.03	30	235	<5	3.46	2	19	405	64	4.82	2.41	20	1.76	1206	34	0.11	78	800	38	10	<20	191	0.11	<10	238	<10	8	192
36	S07-04854	0.6	7.19	15	705	<5	1.88	<1	14	203	86	3.59	1.64	10	1.99	751	3	0.80	21	590	22	<5	<20	127	0.16	<10	153	<10	7	95
45	S07-04863	0.7	5.97	20	65	<5	2.72	3	17	199	152	4.39	2.05	20	1.32	641	27	0.63	38	950	22	<5	<20	122	0.15	<10	366	<10	7	303
54	S07-04872	0.5	7.17	30	185	<5	3.13	<1	10	160	80	2.90	1.66	20	1.42	688	3	0.79	18	620	16	<5	<20	132	0.17	<10	117	<10	10	55
Resplit:																														
1	S07-04819	0.9	4.94	360	955	<5	4.37	1	29	661	64	5.08	1.31	10	2.43	1224	15	0.19	247	790	36	10	<20	257	0.07	<10	218	<10	8	168
36	S07-04854	0.5	7.32	20	690	<5	1.78	<1	15	218	91	3.92	1.76	20	1.93	724	2	0.82	23	610	20	5	<20	118	0.16	<10	151	<10	7	91
Standard:																														
Stsd3		0.5	5.88	30	1310	<5	2.58	1	17	61	44	4.17	1.37	40	1.28	2561	6	1.19	33	1750	46	5	<20	257	0.37	<10	124	<10	33	206
Stsd3		0.4	5.95	25	1390	<5	2.53	1	17	63	43	4.16	1.39	40	1.32	2589	6	1.15	32	1690	52	<5	<20	261	0.35	<10	121	<10	32	201

ICP: 4 ACID DIGEST/ICP-FINISH
 AG: 4 ACID DIGEST/AA-FINISH

JJ/nl
 df/td2135s
 XLS/07


 ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2170

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

13-Feb-08

Attention: Bob Singh

No. of samples received: 71

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-128

Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-04882	0.05	0.001
2	S07-04883	0.03	0.001
3	S07-04884	<0.03	<0.001
4	S07-04885	0.31	0.009
5	S07-04886	<0.03	<0.001
6	S07-04887	<0.03	<0.001
7	S07-04888	0.03	0.001
8	S07-04889	<0.03	<0.001
9	S07-04890	<0.03	<0.001
10	S07-04891	0.17	0.005
11	S07-04892	6.61	0.193
12	S07-04893	<0.03	<0.001
13	S07-04894	<0.03	<0.001
14	S07-04895	0.16	0.005
15	S07-04896	<0.03	<0.001
16	S07-04897	<0.03	<0.001
17	S07-04898	<0.03	<0.001
18	S07-04899	<0.03	<0.001
19	S07-04900	<0.03	<0.001
20	S07-04901	<0.03	<0.001
21	S07-04902	0.03	0.001
22	S07-04903	<0.03	<0.001
23	S07-04904	0.06	0.002
24	S07-04905	<0.03	<0.001
25	S07-04906	<0.03	<0.001
26	S07-04907	<0.03	<0.001


30g FA

ECO TECH LABORATORY LTD.
Jutta Jealousé
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	S07-04908	<0.03	<0.001
28	S07-04909	<0.03	<0.001
29	S07-04910	<0.03	<0.001
30	S07-04911	<0.03	<0.001
31	S07-04912	<0.03	<0.001
32	S07-04913	<0.03	<0.001
33	S07-04914	<0.03	<0.001
34	S07-04915	<0.03	<0.001
35	S07-04916	<0.03	<0.001
36	S07-04917	<0.03	<0.001
37	S07-04918	<0.03	<0.001
38	S07-04919	<0.03	<0.001
39	S07-04920	<0.03	<0.001
40	S07-04921	<0.03	<0.001
41	S07-04922	<0.03	<0.001
42	S07-04923	<0.03	<0.001
43	S07-04924	<0.03	<0.001
44	S07-04925	2.00	0.058
45	S07-04926	<0.03	<0.001
46	S07-04927	<0.03	<0.001
47	S07-04928	<0.03	<0.001
48	S07-04929	<0.03	<0.001
49	S07-04930	0.12	0.003
50	S07-04931	<0.03	<0.001
51	S07-04932	<0.03	<0.001
52	S07-04933	<0.03	<0.001
53	S07-04934	<0.03	<0.001
54	S07-04935	<0.03	<0.001
55	S07-04936	<0.03	<0.001
56	S07-04937	<0.03	<0.001
57	S07-04938	0.13	0.004
58	S07-04939	<0.03	<0.001
59	S07-04940	0.05	0.001
60	S07-04941	0.03	0.001
61	S07-04942	<0.03	<0.001
62	S07-04943	<0.03	<0.001
63	S07-04944	0.20	0.006
64	S07-04945	<0.03	<0.001
65	S07-04946	<0.03	<0.001
66	S07-04947	<0.03	<0.001
67	S07-04948	<0.03	<0.001
68	S07-04949	<0.03	<0.001
69	S07-04950	<0.03	<0.001
70	S07-04951	<0.03	<0.001
71	S07-04952	<0.03	<0.001

= 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
-------	-------	-------------	--------------

QC DATA:**Resplit:**

1	S07-04882	<0.03	<0.001
36	S07-04917	<0.03	<0.001
71	S07-04952	<0.03	<0.001

Standard:

OXi54		1.84	0.054
OXi54		1.86	0.054
OXi54		1.86	0.054
OXi54		1.88	0.055
OXi54		1.90	0.055
OXi54		1.84	0.054

* = 30g FA

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

IJ/sa
(LS/07)


ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

ECO TECH LAB
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS 2007- 2170

Skygold Ventures
615 - 800 W. Pender Street
Vancouver, BC
V6B 2V6

No. of samples received: 71
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-128
Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-04882	0.4	7.85	20	1080	<5	3.97	<1	18	117	84	4.92	1.74	20	1.69	1250	2	1.42	22	1110	30	<5	<20	204	0.21	<10	157	<10	8	100
2	S07-04883	0.3	8.39	20	950	<5	4.52	<1	20	129	73	4.83	2.13	20	1.72	1393	<1	1.46	25	1180	34	<5	<20	252	0.21	<10	158	<10	6	109
3	S07-04884	0.5	9.24	20	720	<5	5.28	<1	22	155	69	5.93	1.54	<10	1.95	1521	<1	1.67	23	900	52	<5	<20	384	0.19	<10	205	<10	5	96
4	S07-04885	0.4	8.82	25	680	<5	5.32	<1	21	82	71	5.79	1.45	<10	1.99	1392	<1	2.02	21	830	30	<5	<20	309	0.18	<10	218	<10	5	61
5	S07-04886	<0.2	9.03	25	455	<5	5.79	<1	28	46	25	8.47	1.42	20	2.23	1520	<1	3.35	19	2370	28	<5	<20	441	0.36	<10	232	<10	15	60
6	S07-04887	0.4	8.45	25	300	<5	5.05	<1	25	102	262	7.69	1.16	20	1.73	1264	<1	1.96	17	1870	26	<5	<20	513	0.33	<10	230	<10	13	91
7	S07-04888	0.4	8.96	30	590	<5	6.63	<1	26	60	112	7.66	1.56	10	2.02	1417	<1	2.08	19	1660	30	<5	<20	571	0.25	<10	239	<10	11	74
8	S07-04889	0.5	>10	25	855	<5	6.33	<1	25	52	127	6.98	1.53	20	1.84	1323	<1	2.25	18	1610	34	<5	<20	535	0.27	<10	242	<10	10	58
9	S07-04890	<0.2	>10	25	820	<5	6.60	<1	26	35	10	7.45	1.49	20	2.27	1462	<1	2.16	19	1720	34	<5	<20	493	0.33	<10	278	<10	12	49
10	S07-04891	0.4	9.28	25	475	<5	6.16	<1	27	54	63	8.97	1.67	20	2.35	1436	4	2.62	20	2160	30	<5	<20	506	0.32	<10	268	<10	15	66
11	S07-04892	6.2	4.21	180	200	<5	0.39	<1	8	42	61	3.70	3.13	<10	0.29	248	14	0.51	24	410	24	70	<20	78	0.31	<10	54	<10	11	53
12	S07-04893	<0.2	7.24	10	280	<5	4.21	<1	20	88	61	6.74	1.01	20	1.81	1308	1	3.41	15	1630	22	<5	<20	349	0.34	<10	176	<10	15	52
13	S07-04894	0.2	7.35	20	1005	<5	3.43	<1	16	134	60	5.36	1.01	20	1.67	1153	<1	1.60	17	1110	20	<5	<20	259	0.26	<10	145	<10	11	88
14	S07-04895	0.3	7.41	15	740	<5	5.25	<1	16	75	90	5.36	1.01	10	1.65	1138	2	2.55	23	1000	28	<5	<20	286	0.23	<10	193	<10	6	66
15	S07-04896	0.2	7.22	30	585	<5	4.59	<1	16	145	75	4.94	1.06	10	1.47	1152	2	2.58	22	1090	30	<5	<20	297	0.25	<10	122	<10	11	84
16	S07-04897	<0.2	8.38	20	865	<5	4.41	<1	17	70	80	5.39	1.60	<10	1.74	1304	<1	2.57	24	860	28	<5	<20	306	0.22	<10	177	<10	6	77
17	S07-04898	0.3	8.40	20	605	<5	3.97	<1	17	62	70	5.24	1.16	<10	1.72	1162	<1	2.69	20	880	26	<5	<20	312	0.24	<10	171	<10	6	66
18	S07-04899	0.4	8.38	20	515	<5	3.88	<1	21	64	85	5.55	0.99	<10	1.91	1222	<1	2.56	23	910	28	<5	<20	346	0.27	<10	168	<10	6	76
19	S07-04900	<0.2	8.02	20	605	<5	3.75	<1	15	65	67	4.65	1.15	10	1.50	1101	<1	2.20	17	810	24	<5	<20	365	0.26	<10	132	<10	5	69
20	S07-04901	0.2	7.86	15	1250	<5	3.90	<1	17	101	64	5.12	1.81	10	1.69	1131	<1	1.63	22	600	24	<5	<20	362	0.24	<10	152	<10	5	56
21	S07-04902	0.3	8.80	25	675	<5	4.20	<1	22	89	75	5.79	1.90	10	1.83	1132	<1	2.70	21	740	24	<5	<20	405	0.28	<10	190	<10	6	39
22	S07-04903	0.4	8.46	20	690	<5	3.25	<1	17	62	25	4.85	1.56	10	1.46	1066	<1	3.51	15	710	24	<5	<20	384	0.23	<10	160	<10	7	42
23	S07-04904	0.8	8.46	20	715	<5	3.39	<1	18	68	61	5.41	1.55	10	1.67	1106	<1	3.72	17	690	24	<5	<20	371	0.25	<10	183	<10	6	45
24	S07-04905	0.4	8.05	20	625	<5	3.34	<1	23	94	86	5.84	1.48	10	2.09	1156	<1	2.93	30	740	26	<5	<20	327	0.26	<10	181	<10	7	69
25	S07-04906	0.2	8.23	30	615	<5	3.44	<1	24	91	62	6.05	1.45	<10	2.12	1191	<1	3.13	31	780	28	<5	<20	339	0.27	<10	183	<10	7	69

Et #.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	g%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
26	S07-04907	0.2	7.53	25	580	<5	3.38	<1	21	103	69	5.11	1.51	10	2.29	976	<1	2.92	31	720	22	<5	<20	317	0.26	<10	163	<10	8	70
27	S07-04908	0.4	6.94	15	255	<5	2.21	<1	12	107	113	3.96	0.86	10	1.38	683	<1	3.48	16	640	24	<5	<20	262	0.28	<10	96	<10	8	60
28	S07-04909	<0.2	8.23	20	1105	<5	3.76	<1	25	68	126	6.05	1.67	10	2.33	1092	<1	2.86	29	930	30	<5	<20	361	0.32	<10	225	<10	9	74
29	S07-04910	<0.2	8.87	25	805	<5	4.15	<1	25	54	117	6.37	1.11	10	2.40	1215	<1	3.39	30	980	32	<5	<20	350	0.34	<10	294	<10	8	78
30	S07-04911	<0.2	8.24	20	215	<5	3.22	<1	18	53	115	4.84	0.33	10	1.80	933	<1	4.09	19	790	30	<5	<20	362	0.36	<10	179	<10	9	58
31	S07-04912	0.2	8.64	25	290	<5	3.85	<1	27	98	88	6.80	0.46	10	2.94	1293	<1	3.44	46	1120	40	<5	<20	359	0.50	<10	281	<10	15	86
32	S07-04913	0.2	8.58	25	285	<5	3.88	<1	31	87	220	7.22	0.51	10	2.72	1096	<1	3.48	43	1220	30	<5	<20	319	0.55	<10	303	<10	13	79
33	S07-04914	0.2	8.34	20	290	<5	4.16	<1	32	141	250	7.50	0.55	10	3.39	1189	<1	3.28	70	1330	34	<5	<20	321	0.30	<10	337	<10	10	79
34	S07-04915	<0.2	0.72	10	30	<5	>10	<1	<1	<1	4	0.61	0.05	<10	>10	214	<1	0.16	2	170	<2	<5	<20	46	<0.01	<10	4	<10	1	13
35	S07-04916	<0.2	7.90	35	165	<5	3.10	<1	33	191	99	7.20	0.29	10	4.30	1254	<1	3.13	76	1100	28	<5	<20	270	0.16	<10	246	<10	8	79
36	S07-04917	0.5	7.77	20	520	<5	4.09	<1	33	170	183	6.94	0.80	10	3.92	1142	<1	3.05	75	1090	28	<5	<20	310	0.19	<10	340	<10	10	69
37	S07-04918	<0.2	7.23	30	750	<5	5.57	<1	35	232	149	6.86	0.90	10	4.09	1236	<1	2.73	101	1030	22	<5	<20	422	0.13	<10	251	<10	10	64
38	S07-04919	<0.2	7.10	35	845	<5	5.17	<1	41	373	101	7.14	1.06	10	5.18	1336	<1	1.87	130	1480	24	<5	<20	423	0.11	<10	248	<10	10	73
39	S07-04920	<0.2	7.47	35	945	<5	5.01	<1	32	235	84	6.42	1.55	10	4.01	1238	<1	2.16	82	1020	26	<5	<20	438	0.14	<10	247	<10	10	62
40	S07-04921	0.2	8.17	30	1360	<5	3.61	<1	27	71	97	5.80	2.00	10	3.03	1122	<1	2.99	35	1030	24	<5	<20	406	0.23	<10	234	<10	9	64
41	S07-04922	0.2	8.24	30	1370	<5	3.58	<1	28	81	91	6.10	2.37	10	3.06	1115	<1	2.62	38	1030	24	<5	<20	479	0.21	<10	261	<10	8	68
42	S07-04923	0.6	8.60	20	1080	<5	3.77	<1	25	70	117	6.13	2.13	10	2.60	1186	<1	3.10	33	1050	28	<5	<20	473	0.24	<10	228	<10	8	64
43	S07-04924	<0.2	8.74	25	1970	<5	3.90	<1	26	61	86	6.10	2.65	10	2.94	1439	<1	2.88	32	1070	30	<5	<20	391	0.23	<10	244	<10	8	62
44	S07-04925	4.6	4.32	110	325	<5	0.49	1	13	34	645	5.28	2.12	10	1.63	391	15	0.25	25	470	84	45	<20	56	0.28	<10	56	<10	13	622
45	S07-04926	<0.2	8.75	25	2295	<5	3.60	<1	22	58	74	5.91	1.12	10	3.00	1442	<1	2.68	29	1070	26	<5	<20	340	0.23	<10	235	<10	8	61
46	S07-04927	0.2	8.10	20	1575	<5	2.38	<1	25	108	110	6.03	1.20	10	2.80	1183	<1	2.29	32	1010	24	<5	<20	269	0.24	<10	212	<10	7	81
47	S07-04928	0.2	8.31	40	940	<5	3.87	<1	20	104	113	5.67	1.16	10	2.64	1286	30	3.25	30	1080	30	<5	<20	335	0.22	<10	204	<10	10	62
48	S07-04929	<0.2	7.52	30	2115	<5	4.57	<1	23	209	77	5.57	1.31	10	3.40	1770	<1	1.99	62	980	22	5	<20	356	0.19	<10	217	<10	10	53
49	S07-04930	0.8	6.97	30	680	<5	3.04	<1	19	252	81	5.23	1.11	10	2.66	1364	3	1.61	41	970	24	10	<20	237	0.18	<10	177	<10	8	72
50	S07-04931	0.2	7.77	25	3160	<5	2.50	<1	24	103	133	5.60	1.25	10	2.48	1375	<1	1.57	32	1120	24	<5	<20	209	0.25	<10	192	<10	9	76
51	S07-04932	0.2	8.05	25	960	<5	4.43	<1	22	112	91	6.07	1.16	20	2.88	1599	<1	1.62	32	1320	30	<5	<20	335	0.25	<10	182	<10	11	60
52	S07-04933	0.2	7.75	15	1305	<5	3.41	<1	25	127	92	5.93	1.32	10	3.30	1889	<1	2.68	36	1060	24	<5	<20	314	0.21	<10	211	<10	9	56
53	S07-04934	0.2	7.39	20	900	<5	2.61	<1	24	111	92	5.63	1.25	10	3.19	1478	<1	2.51	33	940	24	<5	<20	250	0.19	<10	196	<10	7	88
54	S07-04935	0.4	7.30	25	920	<5	2.39	<1	23	198	74	5.96	1.37	10	2.80	1587	<1	1.12	37	890	28	<5	<20	210	0.19	<10	187	<10	7	115
55	S07-04936	0.6	5.66	40	1265	<5	2.67	<1	13	274	99	3.50	1.25	20	1.41	1142	2	0.27	58	560	26	<5	<20	179	0.17	<10	106	<10	9	128
56	S07-04937	0.4	6.07	55	1405	<5	2.14	<1	13	224	75	3.59	1.27	20	1.52	930	2	0.37	69	500	22	<5	<20	142	0.17	<10	113	<10	8	145
57	S07-04938	0.6	5.75	25	705	<5	4.19	<1	15	187	88	3.66	1.20	20	1.63	1787	<1	0.64	46	670	26	<5	<20	254	0.17	<10	127	<10	10	109
58	S07-04939	0.4	5.72	80	1110	<5	1.50	<1	16	223	71	3.75	1.29	20	1.58	697	<1	0.33	92	490	26	<5	<20	115	0.16	<10	99	<10	7	163
59	S07-04940	0.5	5.43	60	450	<5	2.58	<1	15	286	100	3.70	1.27	20	1.71	951	<1	0.45	65	510	28	<5	<20	201	0.13	<10	111	<10	8	106
60	S07-04941	0.6	5.27	50	915	<5	2.07	<1	13	194	72	3.16	1.26	20	1.44	842	<1	0.35	62	440	28	<5	<20	154	0.15	<10	94	<10	7	113
61	S07-04942	<0.2	1.00	5	415	<5	>10	<1	<1	4	2	0.63	0.47	<10	>10	231	<1	0.11	2	200	4	<5	<20	61	<0.01	<10	5	<10	2	18
62	S07-04943	0.2	5.28	60	960	<5	2.06	<1	9	205	80	2.93	1.57	20	1.47	958	<1	0.43	61	450	24	<5	<20	149	0.15	<10	89	<10	7	133
63	S07-04944	1.4	5.15	60	255	<5	2.47	<1	11	221	146	3.55	1.52	20	1.49	1291	1	0.47	54	480	32	<5	<20	174	0.16	<10	85	<10	7	112
64	S07-04945	0.7	4.66	55	865	<5	2.46	<1	11	333	95	2.75	1.50	20	1.53	2228	<1	0.26	64	390	26	<5	<20	193	0.15	<10	85	<10	6	100
65	S07-04946	0.8	4.80	85	790	<5	1.83	<1	18	288	79	3.45	1.46	20	1.83	2789	<1	0.22	118	350	32	<5	<20	155	0.16	<10	85	<10	6	146

Et #.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
66	S07-04947	0.6	4.52	60	705	<5	1.63	<1	16	310	72	2.82	1.13	20	1.48	2168	<1	0.21	87	340	24	<5	<20	134	0.13	<10	76	<10	6	169
67	S07-04948	0.2	3.92	25	640	<5	2.36	<1	6	461	26	1.88	1.09	20	0.92	1128	1	0.38	23	370	20	<5	<20	182	0.11	<10	41	<10	6	51
68	S07-04949	0.4	4.02	30	480	<5	3.23	<1	6	255	25	1.68	1.17	20	0.99	826	3	0.42	25	430	20	<5	<20	202	0.14	<10	46	<10	7	95
69	S07-04950	0.2	3.46	5	440	<5	2.67	<1	4	277	14	1.62	1.29	20	1.01	587	<1	0.54	14	400	14	<5	<20	200	0.15	<10	35	<10	7	43
70	S07-04951	0.2	3.63	10	465	<5	2.58	<1	4	221	13	1.55	1.27	20	0.99	600	<1	0.58	15	390	12	<5	<20	195	0.16	<10	37	<10	7	42
71	S07-04952	0.2	3.99	10	555	<5	2.48	<1	7	380	35	1.83	1.32	30	0.97	575	3	0.41	25	410	14	<5	<20	184	0.15	<10	74	<10	7	80

QC DATA:

Repeat:

1	S07-04882	0.4	8.04	15	1035	<5	3.98	<1	17	112	88	5.30	1.86	20	1.64	1148	2	1.49	21	1050	30	<5	<20	188	0.19	<10	154	<10	8	82
10	S07-04891	0.4	9.48	30	460	<5	6.23	<1	31	54	65	8.96	1.76	20	2.37	1515	4	2.61	20	2210	30	<5	<20	516	0.32	<10	263	<10	15	68
19	S07-04900	<0.2	7.57	15	605	<5	3.65	<1	13	63	68	4.41	1.18	10	1.49	1070	<1	2.17	16	790	26	<5	<20	354	0.26	<10	134	<10	5	69
36	S07-04917	<0.2	8.08	30	525	<5	4.03	<1	34	170	187	7.29	0.85	10	3.98	1164	<1	3.22	78	1100	26	<5	<20	319	0.19	<10	343	<10	10	72
45	S07-04926	<0.2	8.70	20	2285	<5	3.56	<1	23	60	72	5.78	1.19	10	2.97	1444	<1	2.77	27	1070	24	<5	<20	345	0.24	<10	235	<10	8	62
54	S07-04935	0.4	6.97	35	930	<5	2.37	<1	21	213	76	5.76	1.71	10	2.82	1539	<1	1.11	36	870	28	5	<20	210	0.18	<10	185	<10	7	111

Resplit:


1	S07-04882	0.3	8.10	20	1020	<5	3.88	<1	16	110	73	5.19	2.07	20	1.63	1216	<1	1.45	19	1070	28	<5	<20	190	0.20	<10	157	<10	7	94
36	S07-04917	<0.2	7.61	25	475	<5	3.82	<1	31	167	194	6.46	0.74	10	3.90	1121	<1	2.86	70	1070	26	<5	<20	317	0.18	<10	329	<10	10	69
71	S07-04952	0.3	3.98	15	575	<5	2.44	<1	7	394	40	1.82	1.59	30	0.99	543	4	0.41	27	410	18	<5	<20	185	0.14	<10	83	<10	7	75


Standard:

STSD3	0.4	5.71	30	1465	<5	2.47	<1	18	66	45	4.15	1.40	40	1.27	2612	8	1.25	35	1730	62	<5	<20	261	0.37	<10	120	<10	30	201
STSD3	0.4	5.80	25	1445	<5	2.51	<1	18	63	47	4.20	1.30	40	1.25	2617	9	1.24	34	1700	58	<5	<20	261	0.37	<10	123	<10	30	207
STSD3	0.5	5.81	25	1370	<5	2.47	<1	16	61	41	4.13	1.39	30	1.29	2520	9	1.15	32	1640	58	<5	<20	264	0.34	<10	119	<10	32	198

ICP: 4 ACID DIGEST/ICP-FINISH
 AG: 4 ACID DIGEST/AA-FINISH

JJ/nl
 dt/d2170s
 XLS/07


 ECO TECH LABORATORY LTD.
 Jutta Jalouse
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2183

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

21-Feb-08

Attention: Bob Singh

No. of samples received: 172

Sample Type: Core

Project: Spanish Mountain


Shipment #: SMC-07-129

Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-18479	<0.03	<0.001
2	S07-18480	0.14	0.004
3	S07-18481	<0.03	<0.001
4	S07-18482	<0.03	<0.001
5	S07-18483	<0.03	<0.001
6	S07-18484	<0.03	<0.001
7	S07-18485	<0.03	<0.001
8	S07-18486	<0.03	<0.001
9	S07-18487	<0.03	<0.001
10	S07-18488	<0.03	<0.001
11	S07-18489	<0.03	<0.001
12	S07-18490	<0.03	<0.001
13	S07-18491	0.05	0.001
14	S07-18492	<0.03	<0.001
15	S07-18493	<0.03	<0.001
16	S07-18494	<0.03	<0.001
17	S07-18495	0.06	0.002
18	S07-18496	0.03	0.001
19	S07-18497	<0.03	<0.001
20	S07-18498	0.04	0.001
21	S07-18499	<0.03	<0.001
22	S07-18500	<0.03	<0.001
23	S07-18501	0.08	0.002
24	S07-18502	<0.03	<0.001
25	S07-18503	<0.03	<0.001
26	S07-18504	<0.03	<0.001
27	S07-18505	<0.03	<0.001

* = 30g FA



ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)	
28	S07-18506	<0.03	<0.001	
29	S07-18507	0.03	0.001	
30	S07-18508	0.04	0.001	
31	S07-18509	<0.03	<0.001	
32	S07-18510	*	0.42	0.012
33	S07-18511	0.29	0.009	
34	S07-18512	0.45	0.013	
35	S07-18513	1.94	0.057	
36	S07-18514	1.07	0.031	
37	S07-18515	0.68	0.020	
38	S07-18516	0.97	0.028	
39	S07-18517	0.31	0.009	
40	S07-18518	0.67	0.020	
41	S07-18519	0.44	0.013	
42	S07-18520	2.25	0.066	
43	S07-18521	1.10	0.032	
44	S07-18522	2.48	0.072	
45	S07-18523	1.66	0.048	
46	S07-18524	*	<0.03	<0.001
47	S07-18525	0.38	0.011	
48	S07-18526	0.22	0.006	
49	S07-18527	0.24	0.007	
50	S07-18528	<0.03	<0.001	
51	S07-18529	0.10	0.003	
52	S07-18530	1.19	0.035	
53	S07-18531	0.59	0.017	
54	S07-18532	0.43	0.013	
55	S07-18533	3.37	0.098	
56	S07-18534	0.86	0.025	
57	S07-18535	0.06	0.002	
58	S07-18536	*	6.69	0.195
59	S07-18537	0.17	0.005	
60	S07-18538	0.71	0.021	
61	S07-18539	0.24	0.007	
62	S07-18540	0.18	0.005	
63	S07-18541	0.29	0.009	
64	S07-18542	0.06	0.002	
65	S07-18543	0.09	0.003	
66	S07-18544	<0.03	<0.001	
67	S07-18545	<0.03	<0.001	
68	S07-18546	<0.03	<0.001	
69	S07-18547	<0.03	<0.001	
70	S07-18548	0.23	0.007	
71	S07-18549	0.50	0.015	
72	S07-18550	0.19	0.006	
73	S07-18551	0.58	0.017	
74	S07-18552	0.19	0.006	
75	S07-18553	*	<0.03	<0.001

* = 30g FA


ECO TECH LABORATORY LTD.

Jutta Jealousé
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
76	S07-18554	0.09	0.003
77	S07-18555	0.04	0.001
78	S07-18556	0.44	0.013
79	S07-18557	<0.03	<0.001
80	S07-18558	0.12	0.003
81	S07-18559	<0.03	<0.001
82	S07-18560	<0.03	<0.001
83	S07-18561	<0.03	<0.001
84	S07-18562	<0.03	<0.001
85	S07-18563	0.03	0.001
86	S07-18564	<0.03	<0.001
87	S07-18565	0.39	0.011
88	S07-18566	*	<0.03
89	S07-18567	<0.03	<0.001
90	S07-18568	<0.03	<0.001
91	S07-18569	0.04	0.001
92	S07-18570	<0.03	<0.001
93	S07-18571	0.54	0.016
94	S07-18572	<0.03	<0.001
95	S07-18573	<0.03	<0.001
96	S07-18574	<0.03	<0.001
97	S07-18575	<0.03	<0.001
98	S07-18576	<0.03	<0.001
99	S07-18577	0.35	0.010
100	S07-18578	<0.03	<0.001
101	S07-18579	0.13	0.004
102	S07-18580	*	2.08
103	S07-18581	0.09	0.003
104	S07-18582	0.44	0.013
105	S07-18583	0.07	0.002
106	S07-18584	0.44	0.013
107	S07-18585	0.06	0.002
108	S07-18586	0.54	0.016
109	S07-18587	<0.03	<0.001
110	S07-18588	0.05	<0.001
111	S07-18589	0.10	0.003
112	S07-18590	0.07	0.002
113	S07-18591	0.24	0.007
114	S07-18592	1.79	0.052
115	S07-18593	0.23	0.007
116	S07-18594	0.15	0.004
117	S07-18595	0.21	<0.001
118	S07-18596	0.06	0.002
119	S07-18597	0.12	0.003
120	S07-18598	*	0.42

* = 30g FA



Eco Tech LABORATORY LTD.

Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
121	S07-18599	0.05	0.001
122	S07-18600	<0.03	<0.001
123	S07-18601	<0.03	<0.001
124	S07-18602	0.04	0.001
125	S07-18603	<0.03	<0.001
126	S07-18604	<0.03	<0.001
127	S07-18605	<0.03	<0.001
128	S07-18606	0.05	0.001
129	S07-18607	0.28	0.008
130	S07-18608	0.12	0.004
131	S07-18609	0.85	0.025
132	S07-18610	0.37	0.011
133	S07-18611	3.12	0.091
134	S07-18612	0.99	0.029
135	S07-18613	8.81	0.257
136	S07-18614	* <0.03	<0.001
137	S07-18615	0.38	0.011
138	S07-18616	0.13	0.004
139	S07-18617	0.86	0.025
140	S07-18618	0.40	0.012
141	S07-18619	0.12	0.003
142	S07-18620	<0.03	<0.001
143	S07-18621	<0.03	<0.001
144	S07-18622	0.44	<0.001
145	S07-18623	* 2.08	0.061
146	S07-18624	<0.03	<0.001
147	S07-18625	0.03	<0.001
148	S07-18626	<0.03	<0.001
149	S07-18627	<0.03	<0.001
150	S07-18628	<0.03	<0.001
151	S07-18629	<0.03	<0.001
152	S07-18630	0.27	<0.001
153	S07-18631	<0.03	<0.001
154	S07-18632	<0.03	<0.001
155	S07-18633	<0.03	<0.001
156	S07-18634	<0.03	<0.001
157	S07-18635	<0.03	<0.001
158	S07-18636	<0.03	<0.001
159	S07-18637	<0.03	<0.001
160	S07-18638	<0.03	<0.001
161	S07-18639	0.05	0.001
162	S07-18640	<0.03	<0.001
163	S07-18641	<0.03	<0.001
164	S07-18642	<0.03	<0.001
165	S07-18643	<0.03	<0.001
166	S07-18644	<0.03	<0.001

= 30g FA



ECO TECH LABORATORY LTD.

 Anil Jaiswal
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
167	S07-18645	<0.03	<0.001
168	S07-18646	<0.03	<0.001
169	S07-18647	0.37	0.011
170	S07-18648	* <0.03	<0.001
171	S07-18649	<0.03	<0.001
172	S07-18650	<0.03	<0.001

QC DATA:**Resplit:**

1	S07-18479	<0.03	<0.001
36	S07-18514	1.39	0.041
71	S07-18549	0.43	0.013
141	S07-18619	0.07	0.002

Standard:

OX154	1.84	0.054
OX154	1.88	0.055
OX154	1.86	0.054
OX154	1.89	0.055
OX154	1.85	0.054
OX154	1.90	0.055
JX154	1.86	0.054
OX154	1.88	0.055
OX154	1.89	0.055
OX154	1.90	0.055
OX154	1.87	0.055
OX154	1.89	0.055
OX154	1.90	0.055

* = 30g FA

JJ/dc
XLS/07


ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

ECO TECH LABORATORY LTD.

10041 Dallas Drive

KAMLOOPS, B.C.

V2C 6T4

Phone: 250-573-5700

Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS 2007- 2183

Skygold Ventures

615 - 800 W. Pender Street

Vancouver, BC

V6B 2V6

No. of samples received: 172

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-129

Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-18479	0.8	5.05	215	595	<5	5.43	<1	40	541	34	5.25	2.28	<10	4.79	1450	<1	0.33	249	940	22	10	<20	234	0.07	<10	157	<10	6	63
2	S07-18480	0.2	4.24	260	360	<5	3.75	<1	30	541	17	4.12	2.15	10	2.65	990	<1	0.34	231	490	22	5	<20	153	0.06	<10	73	<10	7	76
3	S07-18481	<0.2	5.38	130	540	<5	4.41	<1	24	404	12	4.37	2.45	20	4.47	1613	<1	0.31	150	590	22	<5	<20	246	0.08	<10	85	<10	9	52
4	S07-18482	0.2	6.16	280	685	<5	7.45	<1	43	551	66	5.90	2.50	<10	2.66	1811	<1	0.31	237	930	32	10	<20	144	0.08	<10	156	<10	7	136
5	S07-18483	<0.2	4.16	240	335	<5	7.01	<1	51	935	30	5.64	1.95	<10	5.37	2152	<1	0.41	324	590	22	<5	<20	193	0.06	<10	129	<10	6	94
6	S07-18484	0.2	4.30	380	65	<5	6.90	<1	74	1175	34	6.66	0.98	<10	7.96	2265	<1	0.45	594	630	30	10	<20	220	0.04	<10	134	<10	6	110
7	S07-18485	0.4	4.81	430	120	<5	7.35	<1	69	1380	48	6.55	1.51	<10	5.52	2189	<1	0.39	528	530	46	15	<20	220	0.04	<10	151	<10	7	163
8	S07-18486	<0.2	3.77	290	150	<5	6.80	<1	57	1085	30	5.92	1.71	<10	8.41	1694	<1	0.36	429	550	20	10	<20	309	0.03	<10	121	<10	6	65
9	S07-18487	0.2	4.03	695	170	<5	7.81	<1	82	1575	19	6.00	2.00	<10	6.72	1666	<1	0.29	753	470	18	15	<20	313	0.03	<10	113	<10	5	93
10	S07-18488	1.0	5.33	265	295	<5	6.12	<1	54	747	162	5.95	2.29	<10	5.81	1462	<1	0.49	301	860	22	25	<20	294	0.06	<10	171	<10	6	82
11	S07-18489	1.6	5.58	160	385	<5	3.89	<1	48	504	75	5.71	2.30	<10	6.91	1235	<1	0.61	261	960	20	25	<20	325	0.08	<10	172	<10	6	58
12	S07-18490	0.4	5.79	65	720	<5	3.95	<1	29	314	97	4.26	2.58	<10	4.89	966	<1	0.49	99	710	22	<5	<20	286	0.08	<10	132	<10	6	39
13	S07-18491	<0.2	4.67	415	545	<5	6.27	<1	45	905	6	4.50	3.06	10	3.72	1643	<1	0.20	332	440	22	10	<20	377	0.05	<10	83	<10	8	141
14	S07-18492	0.2	6.07	225	1285	<5	4.39	<1	22	388	19	3.01	2.85	20	1.74	1487	<1	0.18	139	320	30	<5	<20	207	0.11	<10	58	<10	10	67
15	S07-18493	0.5	5.14	120	1025	<5	3.09	<1	21	274	166	3.47	2.92	10	1.61	1853	2	0.28	68	480	26	<5	<20	141	0.12	<10	73	<10	7	91
16	S07-18494	0.6	5.74	310	1005	<5	1.59	<1	35	478	39	3.98	2.55	10	1.14	1601	<1	0.40	160	480	44	<5	<20	99	0.13	<10	91	<10	7	147
17	S07-18495	1.0	5.96	135	1400	<5	1.18	<1	19	244	79	3.35	2.95	20	0.48	2214	<1	0.16	61	360	50	<5	<20	39	0.15	<10	77	<10	8	180
18	S07-18496	0.6	4.98	280	900	<5	1.94	<1	41	637	76	5.45	2.87	10	1.99	3619	<1	0.16	205	520	42	5	<20	117	0.13	<10	110	<10	6	164
19	S07-18497	0.4	4.63	70	850	<5	0.90	<1	22	154	61	3.61	2.63	20	1.21	2043	<1	0.55	52	380	32	<5	<20	71	0.17	<10	87	<10	6	84
20	S07-18498	0.6	6.28	110	1290	<5	0.91	<1	32	100	43	4.45	3.14	20	1.41	2520	<1	0.62	78	480	32	<5	<20	68	0.20	<10	125	<10	8	128
21	S07-18499	0.4	4.81	75	990	<5	1.50	<1	27	285	75	4.03	2.86	20	2.13	2581	<1	0.20	84	450	26	<5	<20	98	0.16	<10	124	<10	6	110
22	S07-18500	0.6	4.80	70	725	<5	1.57	<1	28	204	131	3.94	2.18	20	1.40	2477	<1	1.01	75	450	32	<5	<20	101	0.17	<10	80	<10	7	85
23	S07-18501	0.4	5.23	65	410	<5	1.12	<1	30	254	78	4.78	1.73	20	1.41	2134	<1	1.33	69	700	34	<5	<20	98	0.17	<10	104	<10	7	101
24	S07-18502	1.0	5.94	20	825	<5	1.98	<1	15	145	307	3.11	2.17	10	2.15	2249	<1	1.26	32	530	26	<5	<20	145	0.13	<10	129	<10	6	83
25	S07-18503	0.5	6.29	35	860	<5	1.97	<1	19	157	136	3.38	2.32	10	2.22	2357	<1	1.34	35	530	24	<5	<20	147	0.13	<10	121	<10	5	92

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn	
26	S07-18504	0.3	4.67	125	280	<5	1.97	<1	27	344	84	3.84	1.86	10	2.98	1419	<1	0.58	129	540	28	<5	<20	130	0.08	<10	67	<10	6	69
27	S07-18505	0.2	5.18	245	600	<5	3.86	<1	29	517	8	4.05	2.28	20	4.09	2083	<1	0.24	195	610	50	5	<20	196	0.06	<10	67	<10	8	126
28	S07-18506	0.2	4.99	255	615	<5	3.08	<1	31	604	29	4.00	2.09	<10	3.22	1711	2	0.17	201	380	24	<5	<20	157	0.07	<10	88	<10	7	141
29	S07-18507	0.4	5.32	100	215	<5	3.43	<1	28	333	110	4.01	1.93	10	2.62	2177	5	0.16	115	760	44	<5	<20	209	0.11	<10	126	<10	8	72
30	S07-18508	0.6	6.15	110	360	<5	6.30	<1	41	320	225	4.67	2.60	10	3.49	4369	<1	0.29	119	730	34	<5	<20	263	0.11	<10	282	<10	8	72
31	S07-18509	0.2	4.40	220	530	<5	3.88	<1	35	561	26	3.56	2.22	<10	3.40	2317	<1	0.18	173	780	32	<5	<20	191	0.07	<10	112	<10	7	185
32	S07-18510	0.9	5.40	195	110	<5	0.24	<1	8	31	34	3.56	4.45	<10	0.29	169	5	0.10	17	430	18	40	<20	35	0.36	<10	65	<10	9	50
33	S07-18511	0.4	5.34	110	205	<5	4.85	<1	31	447	140	5.30	2.43	10	2.91	2865	7	0.23	128	540	46	<5	<20	229	0.09	<10	230	<10	8	109
34	S07-18512	1.0	4.64	30	130	<5	2.55	4	19	259	139	5.07	3.09	20	1.25	789	73	0.07	86	990	42	5	<20	136	0.11	<10	283	<10	8	266
35	S07-18513	0.6	5.04	30	195	<5	3.45	2	13	375	189	3.63	2.55	10	1.68	1003	27	0.19	43	680	24	<5	<20	173	0.09	<10	156	<10	7	165
36	S07-18514	0.6	5.97	30	170	<5	2.72	2	18	279	141	4.17	2.30	20	1.58	650	18	0.27	46	600	30	<5	<20	142	0.13	<10	236	<10	8	210
37	S07-18515	0.3	6.87	30	170	<5	2.22	2	19	287	106	4.32	2.69	20	1.63	603	28	0.50	56	720	36	<5	<20	109	0.16	<10	322	<10	7	256
38	S07-18516	0.8	6.74	35	145	<5	3.57	2	29	358	109	5.09	2.94	10	1.70	986	71	0.45	62	1040	38	<5	<20	154	0.17	<10	266	<10	9	204
39	S07-18517	0.3	7.81	35	385	<5	3.02	<1	12	248	109	4.02	2.60	10	2.16	1017	2	0.43	21	660	38	<5	<20	174	0.16	<10	154	<10	9	130
40	S07-18518	0.6	7.75	30	300	<5	2.64	1	16	258	101	3.75	2.94	10	1.81	783	7	0.37	28	690	42	<5	<20	128	0.17	<10	217	<10	7	170
41	S07-18519	0.6	8.05	25	325	<5	3.61	<1	26	119	151	5.98	2.83	10	2.82	937	<1	0.35	21	780	48	<5	<20	159	0.16	<10	213	<10	7	195
42	S07-18520	1.2	7.07	35	190	<5	3.72	2	17	241	149	4.70	2.98	10	1.78	776	29	0.23	38	820	36	<5	<20	159	0.18	<10	345	<10	9	215
43	S07-18521	0.4	7.25	30	180	<5	4.66	<1	15	332	150	4.10	3.08	20	2.03	1133	10	0.34	21	1010	32	<5	<20	185	0.20	<10	178	<10	10	106
44	S07-18522	0.8	8.12	55	205	<5	4.64	2	25	387	172	5.42	2.66	10	1.76	1227	11	0.47	50	1620	42	<5	<20	183	0.24	<10	271	<10	12	219
45	S07-18523	0.8	5.00	40	170	<5	2.93	3	19	292	117	3.55	2.26	10	1.24	772	32	0.21	48	1200	30	<5	<20	122	0.12	<10	194	<10	10	281
46	S07-18524	<0.2	0.54	5	105	<5	>10	<1	<1	4	4	0.62	0.20	<10	>10	227	<1	0.03	4	160	8	<5	<20	50	<0.01	<10	7	<10	1	21
47	S07-18525	0.6	7.12	55	405	<5	4.22	<1	14	197	239	3.71	3.39	10	1.95	1283	5	0.56	23	1290	32	<5	<20	218	0.14	<10	132	<10	10	85
48	S07-18526	0.4	7.62	20	1150	<5	3.14	<1	16	133	74	4.16	3.66	10	1.96	1036	2	0.93	22	710	34	<5	<20	142	0.14	<10	140	<10	7	111
49	S07-18527	0.4	6.43	25	410	<5	3.10	<1	15	175	67	4.15	3.33	10	2.04	1025	2	0.83	23	660	34	<5	<20	160	0.14	<10	139	<10	9	103
50	S07-18528	0.3	7.24	15	1420	<5	1.99	<1	9	140	47	2.84	3.42	10	1.30	539	3	0.67	18	550	28	<5	<20	87	0.15	<10	97	<10	7	102
51	S07-18529	0.4	5.64	20	445	<5	2.30	<1	11	171	64	3.20	2.09	20	1.26	552	10	0.92	29	620	26	<5	<20	111	0.13	<10	139	<10	5	108
52	S07-18530	0.6	6.18	30	90	<5	2.18	<1	18	153	105	4.74	3.38	10	1.05	492	25	0.76	46	660	28	<5	<20	92	0.13	<10	212	<10	6	121
53	S07-18531	0.4	7.41	40	360	<5	6.01	<1	19	172	91	5.14	2.32	10	2.70	1219	8	1.01	28	820	40	<5	<20	212	0.15	<10	274	<10	10	129
54	S07-18532	0.4	7.00	35	215	<5	4.81	1	25	209	88	5.75	3.74	10	2.07	905	37	0.95	38	810	38	<5	<20	168	0.15	<10	250	<10	8	173
55	S07-18533	0.4	7.56	40	295	<5	3.44	<1	12	299	106	3.36	3.66	20	1.46	709	18	0.52	25	890	32	<5	<20	151	0.17	<10	175	<10	10	115
56	S07-18534	0.4	6.07	45	230	<5	2.53	<1	12	174	69	2.93	4.00	20	1.18	462	15	0.59	23	490	26	<5	<20	109	0.12	<10	125	<10	8	103
57	S07-18535	0.2	5.50	25	300	<5	5.06	<1	9	213	29	2.92	2.79	20	1.44	924	6	1.21	16	680	30	<5	<20	181	0.09	<10	79	<10	12	73
58	S07-18536	6.2	3.96	260	165	<5	0.41	<1	8	42	56	3.48	2.99	<10	0.27	235	12	0.49	24	390	24	75	<20	74	0.30	<10	53	<10	10	61
59	S07-18537	0.4	6.21	45	245	<5	3.24	<1	9	258	41	2.76	2.38	20	1.31	669	3	1.37	23	540	32	<5	<20	141	0.16	<10	118	<10	8	89
60	S07-18538	0.4	5.31	45	220	<5	2.94	<1	12	228	36	2.88	2.15	20	1.15	634	3	1.45	31	450	24	<5	<20	128	0.15	<10	72	<10	9	73
61	S07-18539	0.3	7.60	70	275	<5	4.12	<1	13	248	99	3.70	3.95	20	1.61	927	<1	1.32	18	650	30	<5	<20	146	0.17	<10	120	<10	8	58
62	S07-18540	0.3	7.42	75	250	<5	4.14	<1	13	209	97	3.61	4.19	10	1.59	952	<1	1.30	18	670	26	<5	<20	145	0.16	<10	119	<10	8	63
63	S07-18541	0.3	8.08	70	245	<5	4.24	<1	14	180	92	3.46	3.83	20	1.65	966	4	1.50	15	710	28	<5	<20	150	0.17	<10	119	<10	7	57
64	S07-18542	0.2	5.16	35	435	<5	3.33	<1	7	241	28	2.44	3.17	10	1.39	867	2	0.70	12	360	18	<5	<20	143	0.10	<10	57	<10	8	37
65	S07-18543	<0.2	6.22	30	920	<5	4.25	<1	7	130	34	2.37	3.20	10	1.65	1062	<1	1.37	9	500	22	<5	<20	167	0.11	<10	58	<10	10	116

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Li	g%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn	
66	S07-18544	<0.2	6.19	40	360	<5	3.04	<1	12	188	38	3.03	2.73	20	1.55	699	5	1.65	25	430	22	<5	<20	141	0.15	<10	92	<10	8	95
67	S07-18545	0.2	6.93	45	545	<5	4.13	<1	19	112	97	3.86	3.11	10	2.30	1054	<1	2.05	22	540	22	<5	<20	177	0.17	<10	199	<10	7	64
68	S07-18546	0.4	8.30	35	590	<5	3.38	<1	23	107	89	5.54	3.40	<10	3.08	1060	<1	1.75	23	610	28	<5	<20	158	0.19	<10	213	<10	6	115
69	S07-18547	0.3	6.26	30	190	<5	5.74	<1	18	136	88	5.09	2.51	10	2.10	1695	2	1.91	23	900	26	<5	<20	177	0.13	<10	181	<10	6	88
70	S07-18548	0.4	7.49	30	230	<5	4.94	<1	20	106	121	4.57	2.31	10	1.93	1121	26	1.65	34	800	30	<5	<20	186	0.18	<10	278	<10	10	120
71	S07-18549	0.4	6.65	20	730	<5	2.91	<1	9	133	72	2.62	3.34	20	1.29	587	3	1.07	15	570	26	<5	<20	118	0.18	<10	116	<10	9	71
72	S07-18550	0.2	6.14	20	1290	<5	2.94	<1	8	176	46	2.36	2.98	20	1.20	657	2	1.24	15	460	24	<5	<20	114	0.18	<10	105	<10	8	76
73	S07-18551	0.4	7.04	30	855	<5	3.73	<1	7	151	41	2.54	3.63	10	1.36	851	2	0.74	12	540	32	<5	<20	114	0.18	<10	70	<10	9	75
74	S07-18552	0.2	4.81	25	475	<5	2.02	<1	9	447	40	2.37	2.21	10	0.70	427	16	1.33	21	400	18	<5	<20	92	0.17	<10	117	<10	7	69
75	S07-18553	<0.2	0.92	<5	45	<5	>10	<1	<1	5	2	0.62	0.13	<10	>10	243	<1	0.11	3	170	4	<5	<20	119	<0.01	<10	4	<10	2	15
76	S07-18554	0.2	6.92	20	460	<5	2.31	<1	8	175	43	2.93	3.59	10	1.01	494	<1	0.85	10	450	32	<5	<20	103	0.17	<10	59	<10	9	68
77	S07-18555	0.4	6.92	20	350	<5	2.97	<1	9	151	52	3.49	2.75	20	1.23	617	12	0.86	14	640	34	<5	<20	120	0.18	<10	98	<10	9	87
78	S07-18556	0.4	6.22	50	310	<5	3.49	<1	22	84	110	5.17	4.05	10	1.43	927	2	0.37	20	600	34	<5	<20	158	0.14	<10	126	<10	8	54
79	S07-18557	0.2	6.69	15	925	<5	3.48	<1	11	51	52	4.26	3.66	20	1.52	1223	<1	0.75	11	1040	30	<5	<20	232	0.22	<10	101	<10	8	84
80	S07-18558	<0.2	7.36	20	890	<5	3.85	<1	15	34	48	4.90	3.27	20	1.75	1228	<1	1.19	15	1320	32	<5	<20	308	0.21	<10	125	<10	9	100
81	S07-18559	<0.2	7.39	25	1095	<5	3.20	<1	17	53	69	4.62	2.73	20	1.55	1009	2	1.11	17	1220	34	<5	<20	193	0.22	<10	120	<10	9	102
82	S07-18560	0.2	7.43	25	640	<5	3.07	<1	20	84	74	4.58	2.37	10	1.59	1100	<1	1.55	28	670	30	<5	<20	203	0.21	<10	143	<10	7	115
83	S07-18561	<0.2	7.64	30	680	<5	3.14	<1	18	62	57	4.42	2.33	10	1.59	1078	<1	1.69	23	670	30	<5	<20	181	0.22	<10	138	<10	6	98
84	S07-18562	0.2	8.29	30	825	<5	3.67	<1	19	60	105	5.24	2.15	10	1.83	1151	<1	1.92	21	720	38	<5	<20	207	0.23	<10	196	<10	8	87
85	S07-18563	0.4	7.49	40	175	<5	3.19	<1	25	120	110	5.14	2.05	<10	1.26	947	4	2.04	33	530	34	<5	<20	181	0.21	<10	233	<10	5	53
86	S07-18564	0.5	8.03	35	585	<5	4.14	<1	25	82	112	5.91	1.70	<10	1.91	1282	<1	1.55	25	680	36	<5	<20	245	0.19	<10	202	<10	6	79
87	S07-18565	0.4	8.06	30	740	<5	4.05	<1	20	62	137	5.11	1.58	<10	1.72	1206	<1	2.12	22	670	30	<5	<20	323	0.19	<10	194	<10	6	72
88	S07-18566	<0.2	1.06	15	60	<5	>10	<1	<1	3	4	0.69	0.19	<10	>10	303	<1	0.19	3	170	10	<5	<20	67	<0.01	<10	4	<10	1	18
89	S07-18567	0.4	7.59	35	755	<5	4.25	<1	18	76	113	4.94	1.89	<10	1.78	1078	1	2.19	23	840	32	<5	<20	290	0.19	<10	197	<10	6	97
90	S07-18568	0.2	8.19	35	745	<5	4.09	<1	21	68	115	5.27	1.49	<10	1.78	1280	<1	2.19	26	750	32	<5	<20	341	0.21	<10	206	<10	5	79
91	S07-18569	<0.2	7.96	35	620	<5	4.48	<1	20	80	76	4.61	1.47	<10	1.73	1473	<1	2.42	24	710	30	<5	<20	387	0.19	<10	181	<10	4	70
92	S07-18570	<0.2	7.07	30	275	<5	3.16	<1	20	118	60	4.10	1.07	<10	1.49	1199	<1	3.47	20	540	28	<5	<20	298	0.22	<10	154	<10	4	56
93	S07-18571	0.4	7.83	35	530	<5	4.13	<1	14	79	89	4.03	1.35	10	1.42	1045	<1	2.71	19	920	34	<5	<20	287	0.22	<10	117	<10	7	46
94	S07-18572	0.3	7.99	25	595	<5	3.55	2	18	89	95	4.53	1.28	<10	1.69	993	<1	2.16	22	810	68	<5	<20	339	0.21	<10	162	<10	5	215
95	S07-18573	0.2	7.92	20	480	<5	3.84	<1	19	54	51	4.99	1.20	<10	1.96	1082	<1	2.17	23	770	34	<5	<20	374	0.25	<10	186	<10	5	91
96	S07-18574	<0.2	7.83	25	530	<5	3.72	<1	18	60	49	4.80	1.35	<10	1.90	1024	<1	1.89	20	760	30	<5	<20	390	0.21	<10	190	<10	5	76
97	S07-18575	<0.2	8.00	30	515	<5	3.85	<1	18	56	59	4.95	1.39	<10	1.94	1020	<1	2.05	22	770	30	<5	<20	395	0.21	<10	192	<10	5	79
98	S07-18576	0.2	8.11	20	675	<5	3.78	<1	19	69	70	5.00	1.39	<10	1.89	1000	<1	1.76	22	780	32	<5	<20	290	0.22	<10	183	<10	5	68
99	S07-18577	0.6	7.36	25	645	<5	3.58	<1	23	131	245	4.74	1.40	<10	1.57	948	<1	1.48	23	700	42	<5	<20	225	0.21	<10	187	<10	5	110
100	S07-18578	0.2	8.35	25	695	<5	3.86	<1	18	76	65	4.84	1.43	10	1.63	1065	<1	1.87	20	890	36	<5	<20	266	0.23	<10	148	<10	5	77
101	S07-18579	1.2	8.18	20	850	<5	3.89	3	14	87	134	4.26	1.37	<10	1.59	955	<1	1.92	17	740	242	<5	<20	242	0.23	<10	183	<10	5	307
102	S07-18580	4.4	4.67	220	190	<5	0.49	1	12	35	610	5.06	2.70	10	1.61	377	11	0.22	25	470	90	50	<20	53	0.29	<10	56	<10	12	639
103	S07-18581	0.5	8.69	25	935	<5	3.83	<1	24	91	116	5.32	1.46	<10	1.92	982	<1	1.57	29	830	38	<5	<20	238	0.21	<10	230	<10	4	111
104	S07-18582	0.2	8.61	30	930	<5	3.16	<1	20	75	81	4.82	1.70	10	1.76	912	<1	1.32	28	980	36	<5	<20	353	0.22	<10	218	<10	5	110
105	S07-18583	0.2	8.02	50	790	<5	3.91	<1	18	61	75	4.56	1.52	<10	1.56	1020	<1	1.30	22	850	36	<5	<20	344	0.21	<10	167	<10	5	67

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
106	S07-18584	0.4	6.52	50	935	<5	4.08	<1	13	97	117	4.12	1.31	30	0.90	1874	34	0.37	25	1540	68	<5	<20	230	0.31	<10	108	<10	24	116
107	S07-18585	0.2	6.39	55	735	<5	3.45	<1	15	43	91	4.48	1.30	30	0.92	1849	20	0.80	26	1320	46	<5	<20	196	0.31	<10	121	<10	20	116
108	S07-18586	0.2	6.14	55	590	<5	4.43	<1	19	60	42	4.95	1.16	20	0.94	2207	17	0.97	29	1430	44	<5	<20	250	0.32	<10	112	<10	22	105
109	S07-18587	<0.2	6.64	60	590	<5	4.25	<1	17	73	63	4.92	1.23	30	0.99	2279	35	1.13	27	1310	46	<5	<20	276	0.34	<10	109	<10	18	124
110	S07-18588	0.3	6.50	35	535	<5	3.45	<1	13	88	98	4.17	1.10	30	0.86	1703	21	1.09	21	1570	48	<5	<20	266	0.37	<10	85	<10	22	120
111	S07-18589	0.4	6.44	65	655	<5	3.56	<1	12	72	84	4.47	1.40	30	0.90	1716	20	0.83	22	1550	52	<5	<20	225	0.34	<10	90	<10	21	122
112	S07-18590	0.2	6.42	50	670	<5	3.17	<1	9	72	55	3.47	1.13	30	0.72	1565	11	1.05	18	1560	44	<5	<20	212	0.32	<10	98	<10	19	97
113	S07-18591	0.3	5.87	50	645	<5	3.61	<1	8	108	83	3.71	1.14	30	0.83	1816	13	0.83	20	1160	46	<5	<20	140	0.31	<10	82	<10	21	100
114	S07-18592	1.8	6.38	45	760	<5	3.83	4	14	100	207	4.36	1.09	20	0.95	1951	29	0.67	27	1510	530	<5	<20	156	0.37	<10	117	<10	20	922
115	S07-18593	0.2	6.52	35	610	<5	3.72	<1	19	78	61	4.97	1.10	20	1.06	2075	25	0.90	30	1410	54	<5	<20	170	0.39	<10	119	<10	21	148
116	S07-18594	0.3	6.68	50	575	<5	3.13	<1	17	72	117	4.57	1.19	20	0.93	1895	34	0.96	27	1290	54	<5	<20	198	0.35	<10	126	<10	16	198
117	S07-18595	0.6	5.70	55	165	<5	3.05	<1	21	84	119	4.82	1.47	30	0.71	1545	<1	0.93	43	1250	52	<5	<20	153	0.24	<10	116	<10	18	222
118	S07-18596	0.2	4.78	30	665	<5	2.61	<1	9	126	90	3.33	1.22	30	0.62	1704	<1	0.81	26	1170	36	<5	<20	142	0.24	<10	75	<10	21	173
119	S07-18597	0.2	4.71	70	490	<5	3.00	<1	12	204	66	3.39	1.10	40	0.58	1429	<1	0.59	22	1020	40	<5	<20	159	0.23	<10	66	<10	26	130
120	S07-18598	0.8	5.63	230	145	<5	0.29	<1	6	29	33	3.30	4.35	10	0.34	179	4	0.09	19	500	20	40	<20	40	0.54	<10	65	<10	10	60
121	S07-18599	<0.2	5.56	35	655	<5	3.37	<1	13	79	49	4.81	1.16	40	0.85	2253	13	0.61	20	1810	48	<5	<20	153	0.33	<10	71	<10	23	159
122	S07-18600	<0.2	5.66	65	285	<5	3.72	<1	15	103	47	5.40	2.42	40	0.87	2455	22	0.51	20	1980	48	<5	<20	154	0.28	<10	71	<10	30	183
123	S07-18601	0.2	6.08	65	415	<5	4.15	<1	17	104	72	5.13	1.25	40	1.01	2233	3	0.45	40	2010	46	<5	<20	151	0.33	<10	99	<10	31	315
124	S07-18602	0.2	6.10	55	620	<5	3.34	<1	8	74	59	3.07	1.42	50	0.82	1662	<1	0.30	15	1390	44	<5	<20	122	0.27	<10	65	<10	30	213
125	S07-18603	0.2	5.75	30	1320	<5	3.68	<1	9	127	79	3.27	1.26	30	0.99	2005	<1	0.34	22	1000	42	<5	<20	137	0.23	<10	104	<10	26	176
126	S07-18604	<0.2	5.71	30	1315	<5	2.91	<1	7	84	44	2.38	1.18	40	0.83	1415	<1	0.34	17	830	46	<5	<20	118	0.22	<10	66	<10	29	150
127	S07-18605	<0.2	5.72	10	1235	<5	4.13	<1	6	115	29	2.75	1.15	40	1.03	2187	<1	0.24	13	970	48	<5	<20	159	0.19	<10	58	<10	34	159
128	S07-18606	0.2	5.91	45	1440	<5	3.39	<1	8	89	55	2.61	3.29	40	0.90	1628	<1	0.16	17	890	56	<5	<20	126	0.19	<10	64	<10	34	119
129	S07-18607	0.5	5.88	55	930	<5	3.62	<1	9	162	104	3.62	2.77	30	0.84	1811	<1	0.48	21	1980	58	30	<20	197	0.32	<10	106	<10	34	136
130	S07-18608	1.0	5.94	75	435	<5	3.43	<1	16	92	246	5.81	2.90	40	0.90	1997	1	0.94	17	2740	50	85	<20	239	0.50	<10	148	<10	50	158
131	S07-18609	1.0	5.25	100	440	<5	3.25	<1	16	140	246	5.56	2.47	40	0.77	1742	<1	0.85	21	2670	56	20	<20	205	0.48	<10	128	<10	50	233
132	S07-18610	0.7	5.56	165	390	<5	4.41	<1	20	100	222	6.81	2.60	40	0.90	2659	<1	0.95	25	2880	56	25	<20	250	0.44	<10	137	<10	53	147
133	S07-18611	1.5	5.71	75	450	<5	3.80	<1	20	100	232	6.37	2.48	40	0.86	2260	<1	1.08	23	2770	60	30	<20	248	0.43	<10	148	<10	46	159
134	S07-18612	0.9	5.82	70	305	<5	4.55	<1	18	121	228	6.39	2.27	40	0.95	2328	<1	1.02	22	3420	72	<5	<20	279	0.43	<10	142	<10	51	179
135	S07-18613	0.6	5.64	85	270	<5	3.77	7	15	162	108	4.52	3.16	40	0.79	1997	<1	0.58	24	1960	66	<5	<20	207	0.33	<10	100	<10	31	1547
136	S07-18614	<0.2	0.80	15	70	<5	>10	<1	<1	7	4	0.50	0.26	<10	6.35	390	53	0.02	4	410	8	<5	<20	103	0.01	<10	2	<10	7	31
137	S07-18615	0.5	4.49	145	245	<5	2.29	<1	10	164	94	3.33	2.17	30	0.51	1217	<1	0.90	19	860	48	20	<20	160	0.23	<10	66	<10	23	82
138	S07-18616	0.2	6.28	45	650	<5	2.89	<1	17	99	106	4.49	2.49	20	0.73	1854	21	1.46	26	1110	58	<5	<20	215	0.35	<10	107	<10	17	195
139	S07-18617	0.3	6.40	60	515	<5	3.64	<1	13	105	69	4.70	2.53	20	0.82	2049	27	1.18	21	1260	56	10	<20	251	0.35	<10	92	<10	22	100
140	S07-18618	0.4	3.06	110	350	<5	1.99	<1	7	261	62	2.53	1.69	10	0.46	1091	<1	0.18	17	600	20	<5	<20	147	0.17	<10	52	<10	16	179
141	S07-18619	0.3	6.06	65	400	<5	2.90	<1	15	83	53	4.27	2.03	20	0.92	1822	25	1.63	24	1230	46	<5	<20	229	0.34	<10	112	<10	18	92
142	S07-18620	0.4	6.42	45	825	<5	3.03	<1	16	88	134	4.94	2.21	30	1.17	1934	39	1.51	34	1520	44	<5	<20	229	0.37	<10	189	<10	17	111
143	S07-18621	0.6	5.77	65	350	<5	2.99	<1	16	80	159	4.04	1.13	30	0.93	1467	29	1.97	27	1150	50	<5	<20	227	0.33	<10	109	<10	17	68
144	S07-18622	0.6	5.76	75	375	<5	2.87	<1	15	111	177	4.13	1.75	30	0.86	1420	20	1.74	32	1300	60	<5	<20	215	0.35	<10	103	<10	19	67
145	S07-18623	4.5	4.29	205	210	<5	0.50	1	10	29	597	4.92	2.64	20	1.87	404	7	0.12	33	480	152	55	<20	45	0.44	<10	48	<10	43	631

Et #.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	L	Ag%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn	
146	S07-18624	0.4	6.13	55	330	<5	2.74	<1	16	79	211	4.63	1.11	30	1.04	1508	13	1.87	29	1500	48	<5	<20	252	0.41	<10	124	<10	18	75
147	S07-18625	0.7	6.35	60	340	<5	3.10	<1	20	110	195	5.51	1.04	30	1.24	1706	41	1.65	50	1560	52	<5	<20	292	0.46	<10	159	<10	21	97
148	S07-18626	0.2	6.32	35	305	<5	2.81	<1	16	89	155	4.53	0.80	20	1.07	1476	28	1.87	30	1380	46	<5	<20	234	0.53	<10	121	<10	20	77
149	S07-18627	1.0	6.34	30	620	<5	2.67	<1	19	84	394	4.73	2.02	20	1.23	1583	38	1.62	38	1320	48	<5	<20	226	0.47	<10	130	<10	18	96
150	S07-18628	<0.2	5.92	10	470	<5	2.68	<1	9	45	63	3.58	0.87	30	1.26	1510	31	2.11	24	1360	38	<5	<20	233	0.38	<10	100	<10	24	67
151	S07-18629	<0.2	5.90	55	875	<5	3.97	<1	31	234	4	6.34	2.78	30	2.11	2277	34	0.80	118	1710	38	<5	<20	238	0.25	<10	143	<10	28	132
152	S07-18630	0.8	6.31	55	980	<5	3.88	<1	18	128	172	4.98	2.44	20	1.33	1976	24	1.38	42	1360	64	<5	<20	265	0.38	<10	122	<10	27	132
153	S07-18631	0.6	5.37	35	900	<5	3.33	<1	18	183	194	3.88	2.55	20	1.16	1619	6	0.72	45	1280	48	<5	<20	216	0.31	<10	112	<10	28	93
154	S07-18632	0.8	5.75	15	795	<5	2.78	<1	10	61	266	3.66	1.92	20	1.02	1480	23	1.85	26	1250	52	<5	<20	207	0.36	<10	109	<10	21	69
155	S07-18633	0.8	6.28	40	665	<5	3.35	<1	20	108	252	4.29	2.15	30	1.33	1581	<1	1.33	47	1620	44	<5	<20	242	0.32	<10	134	<10	36	81
156	S07-18634	<0.2	6.14	35	1240	<5	4.24	<1	24	174	9	5.49	2.12	20	1.99	2246	43	1.12	85	1670	44	<5	<20	309	0.23	<10	135	<10	29	116
157	S07-18635	0.2	6.62	25	1590	<5	3.06	<1	20	90	79	5.23	3.07	20	1.57	2025	28	1.27	42	1630	50	<5	<20	245	0.37	<10	155	<10	27	104
158	S07-18636	<0.2	6.71	35	1975	<5	2.74	<1	20	91	53	5.20	3.63	30	1.57	2347	43	1.03	41	1620	46	<5	<20	238	0.38	<10	174	<10	22	85
159	S07-18637	0.2	6.92	30	2005	<5	2.78	<1	21	99	67	5.14	3.20	20	1.49	2287	52	1.12	41	1610	50	<5	<20	234	0.42	<10	171	<10	19	88
160	S07-18638	0.2	6.59	55	1740	<5	3.47	<1	23	82	60	5.18	3.39	20	1.73	2824	45	1.01	43	1550	46	<5	<20	283	0.33	<10	145	<10	25	107
161	S07-18639	<0.2	6.22	35	1665	<5	4.24	<1	16	106	24	4.10	3.34	30	1.47	2530	40	0.73	30	2070	48	<5	<20	317	0.33	<10	149	<10	32	48
162	S07-18640	<0.2	6.20	20	1350	<5	3.67	<1	17	80	63	4.31	2.93	20	1.50	2426	43	1.21	33	1650	42	<5	<20	334	0.32	<10	142	<10	26	74
163	S07-18641	0.4	6.48	40	1505	<5	3.46	<1	16	60	85	4.47	2.69	20	1.43	2326	49	1.36	33	1640	54	<5	<20	310	0.37	<10	136	<10	23	78
164	S07-18642	<0.2	6.61	35	1565	<5	2.74	<1	19	68	41	4.86	2.43	20	1.51	2333	36	1.36	37	1510	46	<5	<20	285	0.36	<10	139	<10	20	90
165	S07-18643	<0.2	6.28	30	1565	<5	2.48	<1	19	68	49	4.71	2.47	20	1.52	2246	24	1.29	36	1430	48	<5	<20	286	0.32	<10	140	<10	22	94
166	S07-18644	0.2	6.36	50	1385	<5	2.91	<1	20	87	67	4.36	2.58	20	1.36	2168	41	1.44	36	1430	44	<5	<20	318	0.31	<10	124	<10	26	93
167	S07-18645	<0.2	5.86	65	1355	<5	2.95	<1	19	81	37	4.06	2.47	20	1.33	1985	28	1.42	34	1460	46	<5	<20	310	0.29	<10	118	<10	23	75
168	S07-18646	0.5	5.91	50	1120	<5	2.58	<1	17	97	101	4.21	2.42	20	1.23	1662	24	1.43	30	1400	56	<5	<20	257	0.30	<10	109	<10	23	87
169	S07-18647	0.4	6.01	35	1185	<5	3.29	<1	16	113	91	4.18	3.25	20	1.38	1852	41	1.11	36	1480	54	<5	<20	278	0.31	<10	138	<10	33	76
170	S07-18648	<0.2	0.83	<5	60	<5	>10	<1	<1	3	3	0.52	0.15	<10	6.61	411	54	0.05	4	290	6	<5	<20	47	<0.01	<10	2	<10	6	20
171	S07-18649	0.4	5.67	20	1345	<5	2.44	<1	17	54	137	4.45	1.03	20	1.42	1574	45	1.43	33	1420	52	<5	<20	231	0.25	<10	126	<10	19	95
172	S07-18650	0.4	5.76	50	1405	<5	2.95	<1	18	83	75	4.41	0.98	30	1.47	1697	47	1.38	33	1510	50	<5	<20	297	0.32	<10	142	<10	27	86

QC DATA:


Repeat:

1	S07-18479	0.6	5.10	235	575	<5	5.32	<1	39	544	33	5.21	2.44	<10	4.67	1396	<1	0.33	246	930	22	10	<20	225	0.06	<10	150	<10	6	69
10	S07-18488	1.0	5.07	260	280	<5	5.66	<1	49	705	153	5.51	2.40	<10	5.34	1356	<1	0.45	276	810	24	20	<20	275	0.05	<10	157	<10	5	75
19	S07-18497	0.4	4.70	70	880	<5	0.90	<1	24	152	62	3.82	2.13	20	1.24	2158	<1	0.57	59	400	32	<5	<20	73	0.17	<10	91	<10	6	87
36	S07-18514	0.6	6.08	50	180	<5	2.75	2	17	277	140	4.07	2.35	20	1.56	643	18	0.28	44	580	32	<5	<20	133	0.13	<10	226	<10	8	197
45	S07-18523	0.8	5.11	35	180	<5	3.04	3	19	267	119	3.74	2.49	10	1.24	798	34	0.22	50	1250	32	<5	<20	122	0.12	<10	207	<10	10	283
54	S07-18532	0.4	6.71	40	230	<5	4.72	<1	22	229	92	5.67	3.91	10	2.14	890	31	0.97	31	790	34	<5	<20	175	0.15	<10	252	<10	9	178
71	S07-18549	0.6	6.56	30	765	<5	2.95	<1	10	132	69	2.62	3.40	20	1.25	570	3	1.05	16	570	26	<5	<20	113	0.18	<10	109	<10	8	68
80	S07-18558	<0.2	7.64	25	900	<5	4.02	<1	17	36	48	5.17	1.91	20	1.79	1289	<1	1.14	17	1360	30	<5	<20	310	0.23	<10	125	<10	7	105
89	S07-18567	0.3	7.85	25	755	<5	3.93	<1	18	76	112	4.81	1.57	10	1.66	1084	1	2.17	24	840	48	<5	<20	296	0.21	<10	207	<10	6	96
106	S07-18584	0.4	6.55	50	945	<5	4.09	<1	12	102	118	4.15	1.29	30	0.92	1917	21	0.37	26	1540	74	<5	<20	236	0.31	<10	108	<10	25	116
115	S07-18593	0.2	6.53	40	600	<5	3.80	<1	17	77	63	5.00	1.36	20	1.05	2053	26	0.91	29	1420	58	<5	<20	165	0.36	<10	113	<10	21	146
124	S07-18602	0.2	5.86	65	635	<5	3.12	<1	7	77	59	2.95	2.18	40	0.80	1641	<1	0.26	16	1330	44	<5	<20	120	0.26	<10	61	<10	32	209
141	S07-18619	0.2	6.39	40	410	<5	3.13	<1	16	91	56	4.60	2.06	20	0.95	1937	24	1.71	26	1290	46	10	<20	235	0.36	<10	114	<10	18	97
150	S07-18628	<0.2	5.84	<5	440	<5	2.49	<1	10	46	62	3.52	0.84	30	1.27	1484	30	2.06	22	1320	44	<5	<20	235	0.37	<10	103	<10	23	64
159	S07-18637	0.2	6.51	30	1940	<5	2.57	<1	21	94	66	4.66	3.30	20	1.44	2093	46	1.11	40	1450	52	<5	<20	229	0.38	<10	163	<10	19	85
164	S07-18642	<0.2	6.33	20	1465	<5	2.63	<1	18	67	43	4.49	1.39	20	1.50	2161	26	1.31	32	1450	50	<5	<20	287	0.31	<10	135	<10	18	92


Et #.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	g%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	Y	Zn			
Resplit:																														
36	S07-18479	0.6	5.90	40	180	<5	2.75	2	17	285	137	4.27	2.19	20	1.51	674	18	0.30	42	620	30	<5	<20	132	0.13	<10	233	<10	9	200
71	S07-18514	0.4	6.81	30	710	<5	3.07	<1	10	148	68	2.76	2.02	20	1.38	557	3	0.99	17	570	28	<5	<20	126	0.18	<10	105	<10	9	74
106	S07-18549	1.2	6.51	95	880	<5	4.11	<1	14	100	115	4.42	3.15	30	0.89	1900	36	0.32	29	1570	72	<5	<20	230	0.33	<10	100	<10	25	120
141	S07-18584	0.3	5.66	30	370	<5	2.71	<1	14	81	61	3.94	1.12	20	0.92	1673	30	1.56	20	1170	46	10	<20	232	0.30	<10	109	<10	17	95.2
Standard:																														
STSD3		0.5	5.70	35	1345	<5	2.49	<1	17	58	39	4.05	2.19	30	1.27	2605	7	1.08	33	1680	52	<5	<20	266	0.35	<10	110	<10	30	195
STSD3		0.5	5.88	30	1380	<5	2.48	<1	17	60	40	4.21	1.80	30	1.25	2604	7	1.13	32	1680	54	<5	<20	258	0.35	<10	118	<10	31	193
STSD3		0.5	5.89	25	1300	<5	2.40	<1	17	62	43	4.23	1.39	40	1.31	2585	8	1.14	32	1680	58	<5	<20	264	0.35	<10	120	<10	32	198
STSD3		0.4	5.62	30	1335	<5	2.25	<1	12	55	40	3.95	1.40	40	1.19	2660	6	1.20	38	1700	54	<5	<20	225	0.42	<10	116	<10	33	207
STSD3		0.4	5.44	35	1290	<5	2.27	<1	12	54	41	3.99	1.25	50	1.17	2546	6	1.15	34	1590	60	<5	<20	237	0.40	<10	120	<10	34	205

ICP: 4 ACID DIGEST/ICP-FINISH
 AG: 4 ACID DIGEST/AA-FINISH

JJ/nl
 dl/d2183as/d2183bs
 XLS/07



ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2171

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

18-Feb-08

Attention: Bob Singh

No. of samples received: 70
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-130
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-33177	<0.03	<0.001
2	S07-33178	<0.03	<0.001
3	S07-33179	<0.03	<0.001
4	S07-33180	<0.03	<0.001
5	S07-33181	<0.03	<0.001
6	S07-33182	<0.03	<0.001
7	S07-33183	<0.03	<0.001
8	S07-33184	<0.03	<0.001
9	S07-33185	<0.03	<0.001
10	S07-33186	<0.03	<0.001
11	S07-33187	<0.03	<0.001
12	S07-33188	0.11	0.003
13	S07-33189	0.24	0.007
14	S07-33190	0.26	0.007
15	S07-33191	0.23	0.007
16	S07-33192	0.08	0.002
17	S07-33193	0.43	0.013
18	S07-33194	0.10	0.003
19	S07-33195	0.06	0.002
20	S07-33196	0.11	0.003
21	S07-33197	0.06	0.002
22	S07-33198	0.07	0.002
23	S07-33199	0.06	0.002
24	S07-33200	0.10	0.003
25	S07-33201	0.08	0.002

* = 30g FA

Jutta Jealouse
ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	S07-33202	0.10	0.003
27	S07-33203	0.09	0.003
28	S07-33204	0.15	0.004
29	S07-33205	<0.03	<0.001
30	S07-33206	<0.03	<0.001
31	S07-33207	<0.03	<0.001
32	S07-33208	<0.03	<0.001
33	S07-33209	<0.03	<0.001
34	S07-33210	<0.03	<0.001
35	S07-33211	<0.03	<0.001
36	S07-33212	* <0.03	<0.001
37	S07-33213	0.27	0.008
38	S07-33214	<0.03	<0.001
39	S07-33215	<0.03	<0.001
40	S07-33216	<0.03	<0.001
41	S07-33217	<0.03	<0.001
42	S07-33218	<0.03	<0.001
43	S07-33219	0.03	0.001
44	S07-33220	0.08	0.002
45	S07-33221	0.13	0.004
46	S07-33222	0.15	0.004
47	S07-33223	0.13	0.004
48	S07-33224	* 6.61	0.193
49	S07-33225	0.19	0.006
50	S07-33226	0.19	0.006
51	S07-33227	0.24	0.007
52	S07-33228	0.54	0.016
53	S07-33229	0.17	0.005
54	S07-33230	0.18	0.005
55	S07-33231	0.20	0.006
56	S07-33232	0.19	0.006
57	S07-33233	0.15	0.004
58	S07-33234	0.17	0.005
59	S07-33235	0.15	0.004
60	S07-33236	0.14	0.004
61	S07-33237	0.15	0.004
62	S07-33238	0.10	0.003
63	S07-33239	0.02	0.001
64	S07-33240	0.39	0.011
65	S07-33241	0.98	0.029
66	S07-33242	0.68	0.020
67	S07-33243	0.07	0.002
68	S07-33244	0.26	0.008
69	S07-33245	0.76	0.022
70	S07-33246	0.52	0.015

* = 30g FA

Jutta Jealouse
ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Skygold Ventures AK7-2171

18-Feb-08

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
-------	-------	-------------	--------------

QC DATA:

Resplit:

1	S07-33177	<0.03	<0.001
37	S07-33213	0.43	0.013


Standard:

OXi54		1.88	0.055
OXi54		1.86	0.054
OXi54		1.82	0.053
OXi54		1.90	0.055
OXi54		1.84	0.054

* = 30g FA

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

JJ/sa
XLS/07


Eco Tech LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

31-Jan-08

ICP CERTIFICATE OF ANALYSIS AK 2007- 2171

Skygold Ventures
615 - 800 W. Pender Street
Vancouver, BC
V6B 2V6

TECH LABORATORY LTD.

1 Dallas Drive
ALOOPS, B.C.
26T4

Phone: 250-573-5700
Fax: 250-573-4557

No. of samples received: 70
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-130
Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
1	S07-33177	0.3	5.28	185	340	<5	4.58	<1	58	939	16	5.84	1.38	<10	6.76	1876	<1	0.46	356	570	22	10	197	0.04	<10	140	<10	7	78	
2	S07-33178	1.2	5.39	135	205	<5	1.06	<1	29	494	68	3.63	1.51	20	1.48	1184	<1	1.22	195	600	26	<5	<20	80	0.10	<10	92	<10	9	87
3	S07-33179	0.2	7.41	10	565	<5	2.78	<1	11	70	45	4.17	1.21	10	1.29	802	5	2.37	27	720	26	<5	<20	318	0.38	<10	109	<10	20	56
4	S07-33180	0.3	5.39	45	485	<5	1.56	28	15	221	45	2.77	1.26	20	2.48	793	1	0.88	55	350	36	<5	<20	98	0.09	<10	52	<10	6	1631
5	S07-33181	0.8	4.64	160	235	<5	4.63	1	52	784	43	5.02	1.28	<10	6.61	1896	<1	0.36	351	580	18	5	<20	116	0.05	<10	120	<10	6	216
6	S07-33182	0.2	4.63	75	430	<5	2.62	<1	30	389	32	3.75	1.25	10	4.58	1217	<1	0.32	169	460	16	<5	<20	88	0.09	<10	83	<10	7	62
7	S07-33183	0.8	6.46	100	1125	<5	1.32	<1	28	437	28	3.52	1.53	10	3.48	891	<1	0.32	161	450	20	<5	<20	75	0.10	<10	74	<10	9	108
8	S07-33184	0.4	6.16	135	790	<5	3.88	<1	36	522	36	4.34	1.47	10	4.60	2117	<1	0.34	197	610	24	10	<20	200	0.09	<10	116	<10	7	94
9	S07-33185	0.8	5.95	140	570	<5	2.67	<1	54	704	96	5.85	1.45	10	5.94	1402	<1	0.38	254	760	24	5	<20	137	0.08	<10	148	<10	6	110
10	S07-33186	0.8	5.72	120	560	<5	2.69	<1	42	577	88	5.08	1.34	10	5.74	1450	<1	0.34	217	780	28	5	<20	134	0.09	<10	148	<10	6	96
11	S07-33187	0.5	4.29	245	300	<5	4.27	<1	60	1111	60	5.33	1.35	<10	5.60	2046	16	0.19	461	670	28	10	<20	268	0.05	<10	154	<10	6	108
12	S07-33188	1.6	5.03	55	170	<5	3.65	2	22	225	134	5.00	2.17	20	1.82	926	66	0.12	110	740	38	5	<20	158	0.11	<10	234	<10	10	151
13	S07-33189	3.5	5.09	30	105	<5	3.42	2	19	103	79	5.05	3.68	20	1.50	1102	72	0.10	74	980	66	10	<20	115	0.15	<10	243	<10	9	190
14	S07-33190	2.6	5.00	25	110	<5	2.77	2	17	137	85	4.70	3.83	20	1.49	1150	86	0.13	60	600	58	10	<20	111	0.17	<10	224	<10	10	181
15	S07-33191	1.5	6.44	25	80	<5	2.99	1	25	97	84	5.04	3.55	20	1.43	1428	41	0.14	68	670	58	10	<20	99	0.21	<10	174	<10	10	177
16	S07-33192	0.5	5.66	15	175	<5	2.82	<1	25	113	82	3.82	2.97	20	1.48	1500	21	0.11	68	510	36	<5	<20	108	0.15	<10	148	<10	9	12
17	S07-33193	0.9	5.71	130	330	<5	0.26	<1	8	29	38	3.40	3.90	10	0.33	172	5	0.11	16	440	18	45	<20	40	0.39	<10	75	<10	12	1
18	S07-33194	1.0	6.22	30	90	<5	2.11	<1	34	92	123	4.73	3.11	20	1.15	1253	74	0.15	76	540	48	5	<20	68	0.15	<10	146	<10	8	1
19	S07-33195	0.4	4.92	15	130	<5	1.94	<1	25	79	62	3.25	1.68	20	1.38	1161	8	0.12	53	460	26	<5	<20	80	0.11	<10	109	<10	7	1
20	S07-33196	0.9	5.06	40	175	<5	3.23	1	24	357	115	4.91	1.80	20	1.77	1302	39	0.15	138	590	34	10	<20	125	0.08	<10	188	<10	8	1
						<5	2.54	<1	23	138	149	3.91	1.87	20	2.37	1713	39	0.14	75	430	30	<5	<20	135	0.12	<10	174	<10	9	1
						<5	2.54	<1	21	57	62	3.11	1.80	20	1.44	1491	11	0.19	37	430	38	<5	<20	93	0.14	<10	105	<10	7	1
						<5	2.54	<1	24	357	115	4.91	1.80	20	1.45	1126	16	0.19	59	530	32	<5	<20	94	0.15	<10	136	<10	9	1
						<5	2.54	<1	23	138	149	3.91	1.87	20	1.45	1126	55	0.12	96	940	44	10	<20	143	0.15	<10	251	<10	9	1
						<5	2.54	<1	21	57	62	3.11	1.80	20	1.77	1302	55	0.12	96	940	36	10	<20	115	0.12	<10	280	<10	8	1
						<5	2.54	<1	23	138	149	3.91	1.87	20	1.77	1302	68	0.17	91	900	36	10	<20	115	0.12	<10	280	<10	8	1

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
26	S07-33202	1.0	5.49	30	205	<5	2.76	2	21	249	106	5.93	3.74	20	1.47	993	62	0.16	93	910	38	10	<20	116	0.14	<10	266	<10	8	214
27	S07-33203	2.0	5.41	65	155	<5	2.93	1	20	465	218	6.11	3.70	20	1.66	977	74	0.21	96	870	30	10	<20	128	0.15	<10	280	<10	9	141
28	S07-33204	1.2	6.03	105	250	<5	3.78	<1	35	623	132	5.76	2.14	10	3.74	1458	16	0.59	161	720	44	15	<20	235	0.12	<10	182	<10	7	106
29	S07-33205	0.6	5.38	130	375	<5	3.05	<1	37	695	57	4.35	1.61	<10	4.15	1667	<1	0.33	250	510	24	10	<20	148	0.10	<10	98	<10	6	55
30	S07-33206	0.2	7.01	45	360	<5	3.07	<1	19	374	41	4.12	1.67	10	3.72	1289	<1	0.36	81	620	26	5	<20	148	0.15	<10	94	<10	10	38
31	S07-33207	0.6	5.20	145	325	<5	4.07	<1	34	562	35	4.36	1.23	<10	5.20	1762	<1	0.43	192	480	22	10	<20	203	0.08	<10	88	<10	7	75
32	S07-33208	<0.2	5.60	180	295	<5	3.67	<1	43	677	65	5.08	1.42	<10	5.74	1583	<1	0.58	253	610	20	10	<20	185	0.09	<10	130	<10	6	63
33	S07-33209	0.2	5.63	115	240	<5	6.06	<1	36	474	52	4.62	1.43	<10	6.10	2096	<1	0.71	205	580	22	5	<20	276	0.09	<10	114	<10	9	53
34	S07-33210	0.3	3.79	120	190	<5	4.13	<1	31	614	48	4.40	1.43	<10	5.47	1735	<1	0.36	192	390	20	10	<20	169	0.06	<10	96	<10	4	57
35	S07-33211	0.4	4.91	245	215	<5	6.36	<1	60	874	49	6.05	1.46	<10	7.68	3315	<1	0.56	369	630	26	15	<20	258	0.06	<10	160	<10	6	101
36	S07-33212	<0.2	0.90	<5	50	<5	>10	<1	<1	2	3	0.15	0.10	<10	1.26	58	<1	0.07	25	60	2	<5	<20	5014	<0.01	<10	2	<10	1	3
37	S07-33213	0.8	6.32	45	190	<5	2.63	<1	24	311	178	4.32	1.89	20	1.73	1996	<1	0.95	58	460	36	<5	<20	139	0.16	<10	166	<10	7	94
38	S07-33214	0.4	6.50	75	510	<5	2.96	<1	32	435	129	4.34	1.83	20	3.11	1814	3	1.33	141	690	26	5	<20	146	0.15	<10	134	<10	9	90
39	S07-33215	0.4	5.89	35	190	<5	1.95	<1	14	134	126	2.06	2.12	20	0.97	855	24	1.22	35	310	22	<5	<20	101	0.15	<10	75	<10	8	30
40	S07-33216	<0.2	6.27	75	305	<5	3.49	<1	20	321	55	2.86	1.91	20	2.81	1498	<1	0.85	84	350	20	<5	<20	172	0.14	<10	72	<10	12	41
41	S07-33217	0.5	4.94	135	260	<5	4.33	<1	38	634	63	4.57	1.61	<10	7.01	1885	<1	0.52	237	460	20	10	<20	238	0.06	<10	91	<10	7	101
42	S07-33218	<0.2	4.89	100	375	<5	4.94	<1	34	505	59	3.93	1.97	10	4.64	1786	<1	0.59	194	520	22	5	<20	244	0.08	<10	89	<10	9	65
43	S07-33219	0.2	5.03	65	240	<5	4.78	<1	33	500	82	4.73	1.92	10	3.82	1725	9	0.34	162	630	26	5	<20	256	0.07	<10	145	<10	6	99
44	S07-33220	0.6	4.64	45	140	<5	4.70	1	25	307	69	4.59	1.35	20	2.17	1339	41	0.10	103	630	30	<5	<20	212	0.07	<10	197	<10	8	139
45	S07-33221	1.4	6.34	35	175	<5	3.72	3	25	95	95	6.37	3.84	20	1.50	1153	66	0.11	97	1020	54	15	<20	138	0.10	<10	248	<10	7	274
46	S07-33222	1.1	5.85	20	205	<5	4.26	2	20	156	83	4.31	1.89	20	1.91	1160	32	0.14	75	700	42	5	<20	169	0.10	<10	205	<10	9	184
47	S07-33223	1.4	5.96	35	145	<5	3.24	2	18	97	66	4.19	3.70	20	1.52	918	40	0.15	74	760	48	10	<20	131	0.09	<10	203	<10	8	213
48	S07-33224	6.2	3.97	160	175	<5	0.42	<1	7	44	61	3.59	2.86	<10	0.24	247	10	0.43	23	380	22	75	<20	82	0.31	<10	54	<10	11	60
49	S07-33225	2.0	4.76	25	260	<5	2.49	3	17	151	86	4.57	4.07	20	1.39	818	51	0.11	72	750	54	15	<20	117	0.08	<10	260	<10	7	279
50	S07-33226	2.0	5.26	25	200	<5	2.71	2	20	135	82	4.71	4.07	20	1.39	859	53	0.10	76	880	58	15	<20	125	0.10	<10	271	<10	8	219
51	S07-33227	1.6	5.15	25	105	<5	3.25	3	21	132	81	4.67	4.08	20	1.64	974	45	0.11	81	830	46	10	<20	154	0.09	<10	259	<10	9	268
52	S07-33228	1.2	3.88	20	170	<5	3.00	4	13	128	54	3.69	1.99	10	1.31	952	44	0.04	58	920	80	5	<20	158	0.07	<10	210	<10	7	225
53	S07-33229	1.6	5.26	55	155	<5	4.69	2	25	239	112	5.08	1.91	20	2.24	1464	43	0.13	124	800	58	10	<20	215	0.07	<10	228	<10	10	226
54	S07-33230	1.8	5.41	20	90	<5	3.03	3	18	116	75	4.88	3.99	20	1.48	1038	67	0.09	79	880	74	10	<20	145	0.09	<10	274	<10	8	275
55	S07-33231	1.6	4.89	30	180	<5	2.75	3	17	96	69	4.48	2.00	20	1.22	968	58	0.09	72	750	54	10	<20	125	0.08	<10	249	<10	6	229
56	S07-33232	1.7	5.01	40	200	<5	2.65	2	18	96	74	4.58	1.87	20	1.20	976	67	0.10	75	700	60	10	<20	104	0.08	<10	247	<10	6	230
57	S07-33233	1.4	5.11	25	155	<5	3.18	5	17	125	145	4.15	1.96	20	1.36	1247	53	0.09	65	750	64	10	<20	147	0.11	<10	224	<10	7	386
58	S07-33234	1.3	5.53	35	95	<5	2.49	3	20	71	79	4.50	2.46	10	1.16	959	58	0.13	70	1060	68	10	<20	106	0.09	<10	275	<10	6	285
59	S07-33235	1.6	4.97	60	190	<5	2.20	3	19	86	92	4.35	1.95	20	1.03	811	62	0.11	71	800	58	10	<20	90	0.09	<10	265	<10	6	275
60	S07-33236	1.8	4.92	30	185	<5	2.43	3	21	105	97	4.68	1.94	20	1.11	921	62	0.09	73	900	54	10	<20	93	0.09	<10	265	<10	6	277
61	S07-33237	1.6	4.57	50	85	<5	2.35	3	19	113	91	4.68	3.44	20	1.08	852	63	0.09	73	830	52	10	<20	81	0.09	<10	252	<10	6	284
62	S07-33238	0.8	5.10	65	175	<5	2.45	3	18	101	90	4.26	2.17	20	1.05	850	53	0.14	67	900	38	5	<20	87	0.09	<10	267	<10	6	272
63	S07-33239	0.4	5.40	65	205	<5	2.50	3	15	108	155	3.94	1.74	10	1.13	830	36	0.20	52	1270	26	<5	<20	103	0.10	<10	214	<10	7	212
64	S07-33240	0.3	6.56	30	140	<5	3.42	1	14	104	147	3.54	1.74	20	1.53	864	23	0.50	35	720	22	<5	<20	143	0.12	<10	232	<10	7	139
65	S07-33241	0.2	7.06	35	165	<5	3.44	2	8	96	85	2.96	2.04	20	1.54	796	27	1.02	36	690	28	<5	<20	190	0.17	<10	282	<10	8	181

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
66	S07-33242	0.4	7.35	50	140	<5	2.34	2	12	102	114	4.21	4.05	20	1.59	634	31	0.77	41	690	30	<5	<20	133	0.14	<10	265	<10	7	223
67	S07-33243	0.2	6.93	45	455	<5	1.37	3	16	110	108	3.72	2.00	20	1.66	449	30	0.83	41	790	30	<5	<20	96	0.14	<10	242	<10	6	289
68	S07-33244	0.2	4.96	40	180	<5	2.15	1	16	108	78	3.12	1.61	20	1.27	563	2	0.94	30	610	76	<5	<20	113	0.12	<10	106	<10	6	130
69	S07-33245	0.3	6.15	30	160	<5	2.88	<1	18	116	106	4.17	1.56	20	1.35	642	<1	1.24	31	700	24	<5	<20	131	0.15	<10	116	<10	6	98
70	S07-33246	0.2	5.67	25	180	<5	2.82	<1	14	101	138	3.21	2.02	20	1.36	604	<1	1.08	28	660	20	<5	<20	134	0.13	<10	116	<10	5	73

QC DATA:

Repeat:

1	S07-33177	0.2	5.35	200	345	<5	4.57	<1	58	942	16	5.99	1.28	<10	6.80	1880	<1	0.44	358	570	18	10	<20	202	0.04	<10	140	<10	7	75
10	S07-33186	1.0	5.94	130	600	<5	2.78	<1	40	589	90	5.17	1.41	10	5.89	1488	<1	0.39	220	790	26	5	<20	143	0.09	<10	143	<10	6	100
19	S07-33195	0.5	4.96	15	140	<5	1.98	<1	25	89	63	3.29	1.80	20	1.40	1167	9	0.14	54	460	32	<5	<20	86	0.11	<10	109	<10	7	82
37	S07-33213	0.8	6.29	80	185	<5	2.53	<1	24	325	178	4.32	1.52	20	1.75	1977	<1	0.91	59	470	36	<5	<20	141	0.15	<10	163	<10	8	95
45	S07-33221	1.4	6.17	20	165	<5	3.77	2	22	88	97	6.31	3.99	20	1.49	1097	61	0.10	96	1060	52	10	<20	139	0.07	<10	249	<10	7	296
54	S07-33230	1.8	5.10	25	95	<5	2.79	3	18	111	71	4.53	3.26	20	1.45	1011	63	0.11	74	810	68	10	<20	143	0.09	<10	265	<10	7	264

Resplit:

1	S07-33177	0.2	5.39	210	320	<5	4.69	<1	58	899	14	6.16	1.42	<10	7.11	1940	<1	0.51	378	590	20	10	<20	212	0.05	<10	137	<10	6	77
37	S07-33213	0.6	6.32	55	200	<5	2.53	<1	23	323	178	4.07	2.08	20	1.71	1935	<1	0.91	54	470	32	<5	<20	137	0.15	<10	162	<10	7	84


Standard:

Stsd3		0.5	5.45	40	1460	<5	2.75	<1	19	65	43	4.41	1.42	40	1.37	2599	8	1.17	36	1780	60	<5	<20	284	0.39	<10	117	<10	30	203
Stsd3		0.5	5.78	25	1375	<5	2.47	<1	17	61	42	4.16	1.39	30	1.29	2532	8	1.13	32	1660	56	5	<20	267	0.35	<10	120	<10	32	199

ICP: 4 ACID DIGEST/ICP-FINISH
 AG: 4 ACID DIGEST/AA-FINISH

Jutta Jealouse
 ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

JJ/nl
 dl/d2171s
 XLS/07



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2211

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

29-Feb-08


Attention: Bob Singh

No. of samples received: 75
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-131
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #		Au (g/t)	Au (oz/t)
1	S07-33247	*	<0.03	<0.001
2	S07-33248		0.93	0.027
3	S07-33249		0.49	0.014
4	S07-33250		0.28	0.008
5	S07-33251		<0.03	<0.001
6	S07-33252		0.50	0.015
7	S07-33253		0.28	0.008
8	S07-33254		1.21	0.035
9	S07-33255		0.75	0.022
10	S07-33256		1.10	0.032
11	S07-33257		1.30	0.038
12	S07-33258		1.09	0.032
13	S07-33259		1.65	0.048
14	S07-33260		0.86	0.025
15	S07-33261		0.24	0.007
16	S07-33262		0.53	0.015
17	S07-33263		1.24	0.036
18	S07-33264		0.73	0.021
19	S07-33265	*	2.02	0.059
20	S07-33266		1.09	0.032
21	S07-33267		0.48	0.014
22	S07-33268		1.35	0.039
23	S07-33269		0.69	0.020
24	S07-33270		0.31	0.009
25	S07-33271		1.55	0.045
26	S07-33272		2.16	0.063
27	S07-33273		0.68	0.020
28	S07-33274		<0.03	<0.001
29	S07-33275		<0.03	<0.001
30	S07-33276		0.04	0.001


* = 30g FA


ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
31	S07-33277	0.59	0.017
32	S07-33278	0.46	0.013
33	S07-33279	0.52	0.015
34	S07-33280	0.42	0.012
35	S07-33281	0.43	0.013
36	S07-33282	1.50	0.044
37	S07-33283	* 0.44	0.013
38	S07-33284	1.54	0.045
39	S07-33285	0.87	0.025
40	S07-33286	0.63	0.018
41	S07-33287	13.4	0.391
42	S07-33288	0.84	0.025
43	S07-33289	0.02	0.001
44	S07-33290	0.06	0.002
45	S07-33291	<0.03	<0.001
46	S07-33292	<0.03	<0.001
47	S07-33293	<0.03	<0.001
48	S07-33294	0.03	0.001
49	S07-33295	<0.03	<0.001
50	S07-33296	<0.03	<0.001
51	S07-33297	* <0.03	<0.001
52	S07-33298	1.86	0.054
53	S07-33299	0.41	0.012
54	S07-33300	0.89	0.026
55	S07-33301	1.85	0.054
56	S07-33302	2.64	0.077
57	S07-33303	1.30	0.038
58	S07-33304	1.56	0.046
59	S07-33305	0.38	0.011
60	S07-33306	0.18	0.005
61	S07-33307	0.22	0.007
62	S07-33308	0.11	0.003
63	S07-33309	* 2.10	0.061
64	S07-33310	1.97	0.058
65	S07-33311	0.13	0.004
66	S07-33312	0.76	0.022
67	S07-33313	1.04	0.030
68	S07-33314	0.03	0.001
69	S07-33315	0.95	0.028
70	S07-33316	0.64	0.019
71	S07-33317	0.67	0.020
72	S07-33318	0.27	0.008
73	S07-33319	2.15	0.063

* = 30g FA



ECO TECH LABORATORY LTD.

Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
74	S07-33320	<0.03	<0.001
75	S07-33321	0.13	0.004

QC DATA:**Resplit:**

36	S07-33282	1.86	0.054
71	S07-33317	1.09	0.032

Standard:

Ox154	1.83	0.053
Ox154	1.89	0.055
Ox154	1.88	0.055
Ox154	1.86	0.054
Ox154	1.89	0.055
Ox154	1.88	0.055

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw
XLS/07


ECO TECH LABORATORY LTD.
Jutta Dealouse
B.C. Certified Assayer

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 2007-2211

Skygold Ventures
615 - 800 W. Pender Street
Vancouver, BC
V6B 2V6

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 75
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-131
Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-33247	0.2	0.47	<5	40	<5	>10	<1	2	3	9	0.70	0.10	<10	>10	242	<1	0.15	4	190	16	<5	<20	73	<0.01	<10	3	<10	1	20
2	S07-33248	0.8	5.31	25	125	<5	3.27	<1	14	143	162	3.41	1.31	20	1.49	607	<1	1.23	35	820	30	<5	<20	187	0.12	<10	116	<10	6	49
3	S07-33249	0.8	6.49	20	270	<5	4.73	<1	14	172	122	3.83	1.01	20	1.88	1005	<1	1.48	41	1000	46	<5	<20	236	0.15	<10	124	<10	7	110
4	S07-33250	1.0	5.88	40	205	<5	3.12	<1	14	168	112	3.41	1.05	20	1.33	572	<1	1.36	41	1020	40	<5	<20	181	0.15	<10	117	<10	7	105
5	S07-33251	1.2	5.72	30	330	<5	3.08	<1	21	160	101	4.11	1.02	30	1.37	532	1	1.26	55	1020	38	<5	<20	183	0.12	<10	143	<10	7	116
6	S07-33252	0.6	5.97	45	115	<5	3.37	<1	18	143	106	5.20	1.74	20	1.47	632	<1	1.40	46	800	46	<5	<20	185	0.12	<10	112	<10	7	102
7	S07-33253	1.5	6.37	40	125	<5	3.38	<1	19	173	130	4.81	1.36	20	1.43	542	<1	1.64	49	850	44	<5	<20	185	0.13	<10	128	<10	8	119
8	S07-33254	1.8	4.53	50	90	<5	2.01	1	20	223	149	5.47	1.75	20	0.87	367	132	0.53	99	960	42	<5	<20	102	0.09	<10	246	<10	7	126
9	S07-33255	0.5	4.55	45	110	<5	3.34	2	12	219	80	4.21	1.00	30	1.23	778	11	0.63	56	1580	44	<5	<20	204	0.11	<10	211	<10	9	229
10	S07-33256	1.0	5.70	30	95	<5	3.25	2	18	245	156	4.37	1.16	20	1.35	665	19	1.09	48	1230	40	<5	<20	188	0.13	<10	222	<10	7	208
11	S07-33257	0.8	7.75	30	105	<5	4.47	<1	21	135	107	5.51	1.35	20	2.02	810	6	1.30	47	1110	46	<5	<20	226	0.16	<10	286	<10	7	114
12	S07-33258	0.8	8.87	10	180	<5	5.86	<1	16	97	124	5.67	1.28	10	2.81	1000	<1	0.84	25	1030	58	<5	<20	291	0.16	<10	250	<10	8	131
13	S07-33259	1.2	7.06	35	110	<5	5.01	1	22	217	205	5.95	1.34	20	2.04	915	21	0.76	53	1050	50	<5	<20	234	0.16	<10	285	<10	8	173
14	S07-33260	1.0	5.19	35	115	<5	3.71	2	18	216	124	4.89	1.17	20	1.51	876	21	0.71	53	1270	44	<5	<20	194	0.13	<10	230	<10	7	215
15	S07-33261	0.8	6.00	35	115	<5	4.48	3	16	207	93	5.40	1.30	20	1.83	991	20	0.36	66	910	64	<5	<20	193	0.14	<10	345	<10	8	306
16	S07-33262	0.6	5.87	15	80	<5	4.21	2	17	125	131	5.34	1.15	20	1.88	774	15	0.85	46	1380	64	<5	<20	235	0.14	<10	238	<10	9	205
17	S07-33263	0.8	6.27	35	140	<5	4.30	2	8	103	83	4.14	1.22	20	1.97	845	11	1.13	27	1110	62	<5	<20	239	0.15	<10	200	<10	9	164
18	S07-33264	0.6	6.88	30	95	<5	4.00	1	22	139	86	6.46	1.42	20	1.78	808	8	1.00	47	860	60	<5	<20	210	0.16	<10	183	<10	8	122
19	S07-33265	5.0	4.73	145	290	<5	0.46	2	13	45	646	5.11	1.48	10	1.92	404	9	0.33	32	550	142	60	<20	82	0.30	<10	56	<10	11	701
20	S07-33266	0.8	6.13	25	115	<5	6.90	<1	16	212	93	7.02	1.36	20	2.56	1524	6	0.74	38	1370	60	<5	<20	297	0.12	<10	155	<10	11	121
21	S07-33267	0.6	5.69	40	125	<5	5.38	1	15	158	80	5.40	1.25	20	2.28	1372	5	1.04	29	1180	52	<5	<20	266	0.11	<10	139	<10	9	127
22	S07-33268	1.0	8.05	35	235	<5	3.34	1	14	82	168	4.35	3.33	20	1.80	681	8	1.00	28	1050	60	<5	<20	216	0.18	<10	264	<10	9	154
23	S07-33269	1.0	7.34	65	115	<5	3.60	5	12	219	142	4.20	1.37	20	1.69	734	7	0.67	32	780	86	<5	<20	185	0.17	<10	256	<10	8	418
24	S07-33270	0.6	6.46	25	80	<5	3.40	4	16	184	73	4.50	1.07	20	1.53	792	17	0.63	64	800	64	<5	<20	144	0.15	<10	414	<10	7	383
25	S07-33271	1.2	4.83	80	215	<5	2.05	2	15	252	118	4.74	1.33	20	1.07	599	32	0.16	74	760	54	<5	<20	127	0.09	<10	217	<10	6	163

Et #.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
26	S07-33272	1.0	4.89	75	155	<5	2.55	2	20	305	125	5.97	1.45	20	1.28	789	27	0.14	88	650	60	<5	<20	135	0.09	<10	193	<10	6	173
27	S07-33273	0.8	7.13	85	95	<5	3.14	1	23	128	106	6.92	3.05	20	1.94	774	15	0.70	52	1120	62	<5	<20	152	0.13	<10	224	<10	7	168
28	S07-33274	0.6	8.03	35	165	<5	4.40	<1	20	113	125	5.93	1.54	20	2.39	1023	3	1.73	32	930	54	<5	<20	223	0.16	<10	245	<10	6	137
29	S07-33275	0.8	8.25	35	165	<5	4.27	<1	24	88	130	6.24	1.39	20	2.26	982	4	1.81	38	940	66	<5	<20	216	0.16	<10	253	<10	6	134
30	S07-33276	1.0	7.75	50	110	<5	4.37	1	24	141	118	6.63	1.46	20	2.04	906	5	1.44	37	840	62	<5	<20	220	0.15	<10	314	<10	6	174
31	S07-33277	0.8	7.92	65	80	<5	4.20	<1	21	127	143	6.42	2.77	20	2.15	922	4	0.76	35	760	56	<5	<20	222	0.14	<10	264	<10	6	115
32	S07-33278	1.0	7.03	100	190	<5	4.24	9	20	205	100	5.49	1.87	20	2.00	1028	11	0.42	39	820	290	<5	<20	193	0.14	<10	238	<10	7	813
33	S07-33279	0.8	6.24	40	250	<5	3.17	6	12	361	47	3.81	1.24	20	1.58	978	16	0.19	51	1300	242	<5	<20	216	0.14	<10	202	<10	9	549
34	S07-33280	0.4	6.95	35	140	<5	2.19	<1	13	137	62	4.30	3.17	20	1.65	663	3	0.36	26	540	56	<5	<20	166	0.11	<10	106	<10	7	111
35	S07-33281	0.4	7.48	50	275	<5	2.53	<1	8	198	54	2.79	2.18	20	1.55	606	4	0.55	31	660	58	<5	<20	158	0.16	<10	164	<10	8	107
36	S07-33282	1.2	6.77	45	105	<5	4.03	1	14	146	106	5.87	2.84	20	1.81	812	42	0.55	66	810	60	<5	<20	195	0.14	<10	272	<10	7	170
37	S07-33283	0.8	5.95	170	245	<5	0.27	<1	8	28	44	3.13	4.23	10	0.31	176	3	0.26	21	510	42	45	<20	50	0.38	<10	69	<10	10	53
38	S07-33284	1.0	7.39	25	110	<5	3.60	<1	16	283	92	4.69	2.37	20	1.62	860	19	0.33	46	1100	58	<5	<20	208	0.19	<10	224	<10	8	102
39	S07-33285	0.6	7.48	60	175	<5	4.19	<1	18	197	92	6.20	1.85	10	1.89	951	<1	1.23	23	930	66	<5	<20	236	0.19	<10	135	<10	9	99
40	S07-33286	2.2	8.17	65	275	<5	4.15	<1	19	180	85	6.49	1.70	20	1.58	1121	<1	1.83	24	1150	60	<5	<20	231	0.20	<10	126	<10	9	72
41	S07-33287	2.6	6.77	100	145	<5	3.96	<1	40	307	59	9.08	2.29	20	1.50	1059	16	1.06	59	1980	64	<5	<20	270	0.15	<10	136	<10	9	76
42	S07-33288	0.5	8.73	45	165	<5	3.22	<1	15	201	111	5.05	1.66	20	1.47	943	3	1.27	26	1080	68	<5	<20	187	0.24	<10	147	<10	8	90
43	S07-33289	<0.2	7.81	20	720	<5	3.98	<1	15	194	75	4.60	1.46	20	1.72	1234	<1	2.37	30	920	50	<5	<20	265	0.21	<10	148	<10	6	92
44	S07-33290	0.2	8.07	15	555	<5	4.74	<1	18	191	101	5.99	0.93	10	2.03	1465	2	3.14	32	1000	52	<5	<20	310	0.20	<10	195	<10	6	110
45	S07-33291	0.3	8.70	25	605	<5	4.50	<1	18	131	64	5.32	0.89	10	2.00	1428	<1	3.43	32	960	60	<5	<20	316	0.21	<10	193	<10	5	92
46	S07-33292	0.2	8.24	20	445	<5	4.47	<1	17	166	36	5.06	0.89	10	1.90	1350	<1	3.39	30	1150	54	<5	<20	363	0.22	<10	163	<10	6	66
47	S07-33293	0.3	9.03	30	370	<5	4.11	<1	13	112	66	5.07	0.85	10	1.51	1133	<1	3.64	19	1150	56	10	<20	373	0.20	<10	122	<10	6	68
48	S07-33294	<0.2	8.44	20	310	<5	5.05	<1	17	93	58	5.48	0.91	10	1.95	1077	<1	2.41	26	1040	50	<5	<20	455	0.22	<10	136	<10	6	79
49	S07-33295	0.5	9.15	40	505	<5	4.72	<1	20	140	96	7.12	0.93	10	2.44	1221	<1	1.75	32	1050	54	<5	<20	329	0.21	<10	181	<10	6	94
50	S07-33296	0.4	8.89	25	545	<5	5.87	<1	18	153	76	6.25	1.05	10	2.14	1413	<1	2.61	34	1060	56	<5	<20	363	0.22	<10	185	<10	7	61
51	S07-33297	<0.2	0.30	<5	30	<5	>10	<1	2	3	5	0.52	0.06	<10	>10	185	<1	0.03	3	170	20	<5	<20	1093	<0.01	<10	3	<10	<1	19
52	S07-33298	1.6	6.80	25	260	<5	5.50	<1	23	234	108	7.65	0.90	10	2.05	1556	<1	1.81	32	1280	572	<5	<20	369	0.19	<10	164	<10	8	75
53	S07-33299	0.8	7.95	25	480	<5	5.77	<1	21	175	268	8.04	0.92	20	2.13	1451	<1	1.20	19	1970	64	<5	<20	336	0.38	<10	231	<10	14	99
54	S07-33300	1.4	8.41	30	255	<5	4.01	<1	24	243	283	8.36	1.04	20	1.81	1076	<1	1.63	24	2070	70	<5	<20	301	0.30	<10	229	<10	12	105
55	S07-33301	1.0	7.57	85	225	<5	4.22	<1	23	352	112	8.07	1.14	20	1.64	1202	1	0.71	28	2010	66	<5	<20	317	0.31	<10	188	<10	12	65
56	S07-33302	0.4	7.73	120	175	<5	5.29	<1	33	252	34	>10	2.00	20	1.77	1343	<1	0.81	34	1810	74	<5	<20	372	0.26	<10	196	<10	10	61
57	S07-33303	1.1	5.72	60	210	<5	3.80	<1	20	376	94	5.18	0.92	10	1.20	902	<1	0.30	31	870	136	5	<20	267	0.14	<10	131	<10	6	117
58	S07-33304	2.2	8.12	35	700	<5	4.94	<1	19	220	421	5.51	0.97	10	1.93	1249	<1	1.63	28	970	314	<5	<20	302	0.21	<10	193	<10	7	77
59	S07-33305	0.3	8.64	35	690	<5	4.40	<1	22	127	73	6.30	1.00	10	2.37	1399	<1	1.84	31	840	56	<5	<20	337	0.20	<10	216	<10	5	94
60	S07-33306	0.2	8.11	30	600	<5	4.12	<1	19	148	49	5.76	0.97	<10	2.01	1118	<1	1.87	27	870	50	<5	<20	321	0.19	<10	180	<10	5	69
61	S07-33307	0.4	8.48	40	655	<5	5.04	<1	16	184	75	5.20	1.12	10	1.85	1273	<1	1.61	23	950	64	<5	<20	387	0.20	<10	161	<10	8	52
62	S07-33308	<0.2	7.27	30	755	<5	4.00	<1	7	280	86	3.41	1.19	20	1.30	996	<1	1.10	14	760	50	<5	<20	329	0.16	<10	93	<10	9	29
63	S07-33309	4.8	4.60	220	275	<5	0.47	2	12	41	586	5.26	1.20	10	1.78	399	8	0.29	33	540	126	55	<20	75	0.29	<10	51	<10	10	669
64	S07-33310	1.2	8.50	40	410	<5	5.80	<1	17	214	171	6.73	1.14	20	2.08	1522	<1	1.13	26	1620	196	<5	<20	436	0.28	<10	204	<10	9	141
65	S07-33311	0.4	7.58	25	465	<5	4.67	<1	20	95	271	7.64	0.88	20	1.81	1261	<1	2.69	19	1860	54	<5	<20	470	0.32	<10	216	<10	12	83

Et #.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
66	S07-33312	1.4	9.30	65	245	<5	5.02	<1	24	147	290	9.19	0.89	20	2.00	1396	<1	2.45	22	2170	62	<5	<20	528	0.32	<10	228	<10	11	81
67	S07-33313	1.4	9.17	50	570	<5	5.39	<1	21	120	337	7.29	1.10	20	1.81	1283	<1	1.95	18	2010	64	<5	<20	500	0.36	<10	236	<10	11	71
68	S07-33314	1.0	8.71	20	635	<5	5.40	<1	20	111	240	7.23	1.01	20	1.74	1229	<1	1.45	19	1780	56	<5	<20	404	0.31	<10	210	<10	10	72
69	S07-33315	0.9	8.66	30	385	<5	4.29	<1	21	172	256	7.69	0.98	20	1.67	1104	<1	2.52	20	1770	64	<5	<20	460	0.31	<10	224	<10	11	82
70	S07-33316	0.8	8.89	30	475	<5	5.09	<1	21	181	225	7.58	0.97	10	1.87	1304	<1	2.15	24	1950	62	<5	<20	480	0.32	<10	221	<10	10	64
71	S07-33317	1.2	8.60	15	625	<5	5.30	<1	20	129	377	7.07	1.08	20	1.74	1213	<1	1.14	18	2080	64	<5	<20	356	0.33	<10	233	<10	11	72
72	S07-33318	0.9	8.43	10	495	<5	4.90	<1	19	126	256	6.83	0.96	20	1.61	1055	<1	2.51	18	1850	60	<5	<20	419	0.32	<10	209	<10	10	83
73	S07-33319	1.0	8.03	70	330	<5	5.36	<1	21	173	181	6.84	1.27	20	1.70	1281	<1	1.66	22	1560	78	<5	<20	435	0.33	<10	181	<10	12	75
74	S07-33320	0.6	7.71	10	595	<5	2.66	<1	12	128	61	4.44	1.05	10	1.40	896	<1	3.16	19	740	50	<5	<20	334	0.24	<10	132	<10	5	79
75	S07-33321	0.6	8.17	35	760	<5	3.10	<1	17	116	68	5.15	1.12	10	1.59	1013	<1	2.61	19	830	62	<5	<20	400	0.26	<10	162	<10	5	64

QC DATA:

Repeat:

2	S07-33248	1.0	5.40	30	125	<5	3.35	<1	17	139	152	3.45	1.23	20	1.48	617	<1	1.25	37	830	32	<5	<20	181	0.14	<10	117	<10	6	51
10	S07-33256	0.8	6.04	35	100	<5	3.34	2	19	255	160	4.48	1.26	20	1.38	719	21	1.08	44	1320	44	<5	<20	178	0.14	<10	215	<10	6	220
20	S07-33266	1.0	5.95	25	115	<5	6.96	<1	15	210	98	6.66	1.34	20	2.51	1504	6	0.73	34	1330	56	<5	<20	290	0.11	<10	148	<10	10	110
36	S07-33282	1.1	6.80	50	100	<5	3.69	1	14	140	100	5.78	2.24	20	1.77	825	36	0.49	61	730	54	<5	<20	192	0.14	<10	258	<10	7	165
45	S07-33291	0.4	9.08	20	605	<5	4.67	<1	19	132	66	5.54	0.96	10	2.01	1458	<1	3.50	32	990	58	<5	<20	316	0.22	<10	199	<10	5	104
54	S07-33300	1.6	7.95	35	260	<5	3.76	<1	24	235	281	8.01	1.32	20	1.74	1004	<1	1.55	22	1990	62	<5	<20	285	0.30	<10	221	<10	11	93

Resplit:


2	S07-33248	0.8	5.40	30	120	<5	3.23	<1	15	139	170	3.45	1.39	20	1.51	677	<1	1.28	39	820	32	<5	<20	188	0.12	<10	119	<10	5	48
36	S07-33282	1.1	6.56	40	100	<5	4.18	2	13	139	115	5.74	2.65	20	1.79	796	39	0.61	70	850	64	<5	<20	190	0.15	<10	285	<10	7	179
71	S07-33317	1.2	7.85	15	565	<5	5.34	<1	17	133	382	6.52	1.15	20	1.64	1107	<1	1.15	17	1970	60	<5	<20	340	0.32	<10	211	<10	11	80


Standard:

Stsd3		0.5	5.80	25	1355	<5	2.72	<1	15	63	40	4.18	1.40	40	1.32	2588	6	1.47	47	1710	50	<5	<20	254	0.34	<10	110	<10	28	199
Stsd3		0.5	5.82	25	1360	<5	2.89	<1	17	66	40	4.03	1.31	40	1.35	2610	6	1.42	43	1640	52	<5	<20	256	0.36	<10	115	<10	29	204
Stsd3		0.5	5.77	30	1360	<5	2.66	<1	16	66	41	4.15	1.29	40	1.34	2642	5	1.44	41	1720	56	<5	<20	258	0.35	<10	115	<10	29	203

ICP: 4 ACID DIGEST/ICP-FINISH
 AG: 4 ACID DIGEST/AA-FINISH

JJ/nw
 dt/td2211s
 XLS/07


 ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2212

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

26-Feb-08


Attention: Bob Singh

No. of samples received: 173
Sample Type: Core
Project: **Spanish Mountain**
Shipment #: **SMC-07-132**
Submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-33322	<0.03	<0.001
2	S07-33323	<0.03	<0.001
3	S07-33324	<0.03	<0.001
4	S07-33325	<0.03	<0.001
5	S07-33326	<0.03	<0.001
6	S07-33327	<0.03	<0.001
7	S07-33328	0.10	0.003
8	S07-33329	0.14	0.004
9	S07-33330	0.18	0.005
10	S07-33331	0.24	0.007
11	S07-33332	<0.03	<0.001
12	S07-33333	0.21	0.006
13	S07-33334	0.16	0.005
14	S07-33335	0.20	0.006
15	S07-33336	0.15	0.005
16	S07-33337	0.31	0.009
17	S07-33338	0.29	0.008
18	S07-33339	0.09	0.002
19	S07-33340	0.05	0.002
20	S07-33341	0.16	0.005
21	S07-33342	<0.03	<0.001
22	S07-33343	<0.03	<0.001
23	S07-33344	<0.03	<0.001
24	S07-33345	0.05	0.001
25	S07-33346	0.38	0.011
26	S07-33347	<0.03	<0.001
27	S07-33348	<0.03	<0.001

= 30g FA


ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	S07-33349	<0.03	<0.001
29	S07-33350	<0.03	<0.001
30	S07-33351	<0.03	<0.001
31	S07-33352	<0.03	<0.001
32	S07-33353	* <0.03	<0.001
33	S07-33354	0.34	0.010
34	S07-33355	<0.03	<0.001
35	S07-33356	0.05	0.002
36	S07-33357	<0.03	<0.001
37	S07-33358	<0.03	<0.001
38	S07-33359	<0.03	<0.001
39	S07-33360	<0.03	<0.001
40	S07-33361	<0.03	<0.001
41	S07-33362	<0.03	<0.001
42	S07-33363	<0.03	<0.001
43	S07-33364	* 6.71	0.196
44	S07-33365	0.04	0.001
45	S07-33366	0.03	0.001
46	S07-33367	0.08	0.002
47	S07-33368	0.83	0.024
48	S07-33369	1.13	0.033
49	S07-33370	0.86	0.025
50	S07-33371	0.40	0.012
51	S07-33372	0.11	0.003
52	S07-33373	0.11	0.003
53	S07-33374	1.41	0.041
54	S07-33375	0.17	0.005
55	S07-33376	0.26	0.007
56	S07-33377	0.72	0.021
57	S07-33378	1.17	0.034
58	S07-33379	* <0.03	<0.001
59	S07-33380	2.06	0.060
60	S07-33381	0.97	0.028
61	S07-33382	1.06	0.031
62	S07-33383	1.45	0.042
63	S07-33384	0.38	0.011
64	S07-33385	0.20	0.006
65	S07-33386	8.31	0.242
66	S07-33387	0.39	0.011
67	S07-33388	2.55	0.074
68	S07-33389	0.93	0.027
69	S07-33390	0.73	0.021
70	S07-33391	0.21	0.006
71	S07-33392	0.45	0.013
72	S07-33393	0.51	0.015
73	S07-33394	0.62	0.018
74	S07-33395	1.32	0.038

* = 30g FA



 ECO TECH LABORATORY LTD.

 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #		Au (g/t)	Au (oz/t)
75	S07-33396	*	2.08	0.061
76	S07-33397		1.42	0.041
77	S07-33398		<0.03	<0.001
78	S07-33399		0.19	0.006
79	S07-33400		0.06	0.002
80	S07-33401		0.04	0.001
81	S07-33402		0.29	0.008
82	S07-33403		0.40	0.012
83	S07-33404		0.09	0.003
84	S07-33405		0.05	0.001
85	S07-33406		0.10	0.003
86	S07-33407		0.15	0.004
87	S07-33408		0.08	0.002
88	S07-33409		0.04	0.001
89	S07-33410		0.04	0.001
90	S07-33411		0.05	0.001
91	S07-33412		0.16	0.005
92	S07-33413		0.08	0.002
93	S07-33414		0.21	0.006
94	S07-33415		0.35	0.010
95	S07-33416		0.06	0.002
96	S07-33417		0.06	0.002
97	S07-33418		5.86	0.171
98	S07-33419		0.50	0.015
99	S07-33420		0.14	0.004
100	S07-33421		0.24	0.007
101	S07-33422	*	<0.03	<0.001
102	S07-33423		0.06	0.002
103	S07-33424		0.75	0.022
104	S07-33425		0.07	0.002
105	S07-33426		0.24	0.007
106	S07-33427		0.37	0.011
107	S07-33428		<0.03	<0.001
108	S07-33429		0.54	0.016
109	S07-33430		<0.03	<0.001
110	S07-33431		0.14	0.004
111	S07-33432		0.48	0.014
112	S07-33433	*	0.43	0.013
113	S07-33434		0.52	0.015
114	S07-33435		<0.03	<0.001
115	S07-33436		0.13	0.004
116	S07-33437		0.03	0.001
117	S07-33438		0.17	0.005
118	S07-33439		0.05	0.001
119	S07-33440		0.14	0.004
120	S07-33441		0.10	0.003
121	S07-33442		0.03	0.001

* = 30g FA



ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
122	S07-33443	<0.03	<0.001
123	S07-33444	0.09	0.003
124	S07-33445	0.16	0.005
125	S07-33446	0.20	0.006
126	S07-33447	0.21	0.006
127	S07-33448	0.87	0.025
128	S07-33449	<0.03	<0.001
129	S07-33450	<0.03	<0.001
130	S07-33451	0.04	0.001
131	S07-33452	<0.03	<0.001
132	S07-33453	<0.03	<0.001
133	S07-33454	0.16	0.005
134	S07-33455	0.03	0.001
135	S07-33456	0.14	0.004
136	S07-33457	0.10	0.003
137	S07-33458	1.27	0.037
138	S07-33459	* <0.03	<0.001
139	S07-33460	0.31	0.009
140	S07-33461	0.13	0.004
141	S07-33462	0.03	0.001
142	S07-33463	0.06	0.002
143	S07-33464	0.89	0.026
144	S07-33465	<0.03	<0.001
145	S07-33466	<0.03	<0.001
146	S07-33467	0.05	0.002
147	S07-33468	0.62	0.018
148	S07-33469	* 6.64	0.194
149	S07-33470	0.19	0.006
150	S07-33471	0.19	0.006
151	S07-33472	0.08	0.002
152	S07-33473	<0.03	<0.001
153	S07-33474	<0.03	<0.001
154	S07-33475	0.41	0.012
155	S07-33476	0.05	0.001
156	S07-33477	0.10	0.003
157	S07-33478	0.03	0.001
158	S07-33479	<0.03	<0.001
159	S07-33480	<0.03	<0.001
160	S07-33481	0.05	0.001
161	S07-33482	<0.03	<0.001
162	S07-33483	0.10	0.003
163	S07-33484	0.07	0.002
164	S07-33485	0.25	0.007
165	S07-33486	0.03	<0.001
166	S07-33487	* 2.09	0.061
167	S07-33488	<0.03	<0.001

= 30g FA

ECO TECH LABORATORY LTD.

Jutta Jealous

B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
168	S07-33489	<0.03	<0.001
169	S07-33490	<0.03	<0.001
170	S07-33491	<0.03	<0.001
171	S07-33492	<0.03	<0.001
172	S07-33493	0.05	0.001
173	S07-33494	0.07	0.002

QC DATA:

Resplit:

1	S07-33322	<0.03	<0.001
36	S07-33357	<0.03	<0.001
71	S07-33392	0.52	0.015
106	S07-33427	0.33	0.010
141	S07-33462	0.09	0.003


Standard:

OXi54	1.82	0.053
OXi54	1.89	0.055
OXi54	1.81	0.053
OXi54	1.87	0.055
OXi54	1.84	0.054
OXi54	1.86	0.054
OXi54	1.88	0.055
OXi54	1.81	0.053
OXi54	1.83	0.053
OXi54	1.84	0.054
OXi54	1.87	0.055
OXi54	1.83	0.053
OXi54	1.84	0.054
OXi54	1.86	0.054

* = 30g FA

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

JJ/sa
XLS/07



ECO TECH LABORATORY LTD.

Jutta Jealouse
B.C. Certified Assayer

ECO TECH LABORATORY LTD.

10041 Dallas Drive

KAMLOOPS, B.C.

V2C 6T4

Phone: 250-573-5700

Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS SK 2007-2212

Skygold Ventures

615 - 800 W. Pender Street

Vancouver, BC

V6B 2V6

No. of samples received: 173

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-132

Submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-33322	0.2	5.27	90	725	<5	1.20	<1	14	298	34	2.62	1.34	10	1.33	1423	3	0.19	101	510	30	<5	<20	96	0.14	<10	59	<10	7	103
2	S07-33323	0.4	5.09	300	255	<5	4.34	2	45	1115	70	5.93	1.34	<10	4.32	1528	8	0.32	416	790	28	20	<20	224	0.08	<10	153	<10	6	446
3	S07-33324	0.4	5.89	35	190	<5	1.82	<1	23	373	77	5.00	1.22	<10	5.03	1002	<1	0.85	129	690	24	5	<20	168	0.14	<10	99	<10	7	116
4	S07-33325	0.4	5.05	120	210	<5	4.89	<1	39	705	79	5.51	1.23	<10	7.17	1790	<1	0.49	319	660	30	10	<20	244	0.08	<10	130	<10	6	143
5	S07-33326	0.5	4.81	85	200	<5	5.25	<1	39	695	69	5.25	1.28	<10	6.97	1845	<1	0.46	336	630	24	10	<20	256	0.07	<10	123	<10	6	126
6	S07-33327	0.4	4.38	175	270	<5	6.99	<1	47	1044	103	5.39	1.25	<10	6.12	2068	3	0.29	477	660	22	15	<20	291	0.05	<10	131	<10	6	161
7	S07-33328	1.2	5.20	40	225	<5	3.70	2	24	545	85	5.30	1.61	20	2.53	1125	25	0.23	133	920	40	10	<20	186	0.11	<10	208	<10	7	187
8	S07-33329	1.4	5.03	55	200	<5	3.65	2	21	415	114	4.81	1.41	20	2.62	1107	24	0.19	149	890	40	10	<20	165	0.09	<10	219	<10	7	200
9	S07-33330	1.6	4.80	30	230	<5	4.26	2	22	552	101	4.88	1.37	20	2.22	1197	29	0.14	111	980	52	15	<20	179	0.11	<10	230	<10	7	235
10	S07-33331	2.8	5.01	20	150	<5	2.46	3	16	325	77	5.14	2.29	20	1.38	699	39	0.11	86	930	86	15	<20	111	0.11	<10	265	<10	7	275
11	S07-33332	<0.2	7.23	<5	550	<5	2.69	<1	10	84	37	4.16	1.12	10	1.31	793	3	2.86	30	790	30	<5	<20	386	0.36	<10	105	<10	16	57
12	S07-33333	0.6	4.96	25	195	<5	3.53	3	22	417	71	5.07	1.56	20	2.16	1098	29	0.15	116	840	58	10	<20	173	0.09	<10	227	<10	7	205
13	S07-33334	2.0	4.75	25	235	<5	3.16	3	18	241	81	4.67	1.41	20	1.70	924	32	0.13	90	860	82	10	<20	134	0.09	<10	235	<10	6	187
14	S07-33335	1.8	4.79	30	185	<5	3.25	2	17	363	65	4.71	1.65	20	1.76	924	28	0.15	88	900	56	15	<20	155	0.11	<10	228	<10	7	195
15	S07-33336	1.5	4.97	35	205	<5	4.72	2	22	581	70	5.54	1.53	20	2.50	1286	26	0.17	124	800	50	15	<20	233	0.11	<10	227	<10	8	145
16	S07-33337	1.0	4.81	30	205	<5	4.21	2	22	691	75	5.23	1.45	10	2.19	1238	28	0.15	106	910	48	15	<20	223	0.13	<10	238	<10	7	182
17	S07-33338	2.0	5.50	45	215	<5	2.74	3	20	824	75	5.62	2.24	20	1.40	762	42	0.18	106	960	58	15	<20	126	0.14	<10	303	<10	9	246
18	S07-33339	1.0	5.26	30	170	<5	3.05	3	19	390	66	5.28	2.10	20	1.42	875	34	0.17	91	960	40	10	<20	134	0.13	<10	250	<10	7	232
19	S07-33340	0.5	5.87	40	135	<5	3.13	2	12	377	59	3.60	1.21	20	1.57	727	16	0.50	42	950	28	5	<20	153	0.14	<10	161	<10	8	148
20	S07-33341	0.4	6.37	25	615	<5	2.63	<1	12	199	71	3.29	1.62	10	1.82	629	3	0.86	22	790	26	<5	<20	137	0.15	<10	124	<10	7	77
21	S07-33342	0.2	5.85	25	775	<5	2.37	<1	10	222	52	2.88	1.53	10	1.73	599	4	0.78	24	640	24	<5	<20	136	0.14	<10	129	<10	6	85
22	S07-33343	0.4	5.22	25	725	<5	1.50	1	11	204	49	2.96	1.56	10	1.51	441	6	1.02	29	530	24	<5	<20	107	0.13	<10	150	<10	6	152
23	S07-33344	1.0	5.07	45	530	<5	1.48	1	12	443	46	3.15	0.92	10	1.34	449	7	0.92	31	500	26	5	<20	110	0.14	<10	135	<10	7	149
24	S07-33345	0.6	5.54	35	215	<5	2.09	1	15	180	60	3.39	0.75	20	1.40	581	8	1.00	38	590	30	<5	<20	132	0.13	<10	163	<10	6	146
25	S07-33346	0.6	5.43	85	460	<5	2.58	2	17	433	76	4.50	1.97	20	1.36	629	40	0.84	55	1190	38	5	<20	161	0.13	<10	193	<10	8	200
26	S07-33347	0.4	7.70	55	170	<5	3.11	<1	17	177	79	4.15	2.46	10	2.03	678	3	1.94	28	1360	34	<5	<20	206	0.15	<10	153	<10	8	74
27	S07-33348	<0.2	6.40	60	300	<5	3.53	<1	16	295	55	4.82	1.23	10	2.17	835	1	1.70	25	840	28	<5	<20	210	0.12	<10	117	<10	8	88
28	S07-33349	0.4	7.11	30	555	<5	2.46	<1	14	210	58	4.08	1.00	10	1.99	606	2	1.62	25	690	30	<5	<20	168	0.13	<10	134	<10	7	100
29	S07-33350	0.4	7.18	35	535	<5	2.44	<1	15	289	58	4.66	0.95	10	2.03	661	1	2.11	24	840	30	<5	<20	190	0.16	<10	132	<10	7	72
30	S07-33351	0.6	6.85	40	295	<5	2.83	<1	14	172	45	3.87	1.07	10	1.83	761	1	1.64	22	830	32	<5	<20	176	0.15	<10	127	<10	6	79

Et #.	Tag	Ag	Al%	-As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Ag%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	Y	Zn			
31	S07-33352	0.6	7.33	25	875	<5	3.11	<1	13	157	54	4.12	1.09	10	2.06	779	2	1.70	22	730	30	<5	<20	185	0.14	<10	130	<10	7	81
32	S07-33353	<0.2	0.99	<5	200	<5	>10	<1	<1	5	2	0.73	0.31	<10	>10	248	<1	0.11	3	190	10	<5	<20	78	<0.01	<10	4	<10	1	23
33	S07-33354	0.3	6.70	30	485	<5	5.27	<1	13	126	48	3.99	0.85	20	2.25	1668	4	2.03	21	910	36	<5	<20	266	0.13	<10	122	<10	10	81
34	S07-33355	0.6	6.30	15	735	<5	2.45	<1	12	151	42	3.76	0.92	20	2.01	791	3	1.52	21	670	34	<5	<20	166	0.13	<10	120	<10	7	65
35	S07-33356	0.2	6.45	20	1635	<5	1.84	<1	10	134	54	3.53	1.07	20	1.90	564	3	1.45	21	650	28	<5	<20	136	0.13	<10	124	<10	6	79
36	S07-33357	0.3	6.07	10	1920	<5	1.43	<1	9	240	46	2.80	1.09	20	1.56	455	4	1.28	19	510	32	<5	<20	117	0.14	<10	92	<10	7	83
37	S07-33358	0.4	5.68	20	1355	<5	1.85	<1	10	182	45	2.81	0.89	20	1.36	532	6	1.47	21	630	34	<5	<20	128	0.13	<10	94	<10	7	115
38	S07-33359	0.4	6.50	20	1330	<5	2.02	<1	8	158	43	2.63	1.25	20	1.47	493	6	0.94	20	580	32	<5	<20	129	0.14	<10	114	<10	7	82
39	S07-33360	0.4	5.74	30	1325	<5	1.41	1	11	192	68	3.23	0.90	20	1.40	429	5	1.46	31	610	26	<5	<20	119	0.14	<10	165	<10	5	143
40	S07-33361	0.8	6.39	70	310	<5	1.85	1	20	399	89	5.10	2.35	20	1.68	451	38	0.38	55	750	48	10	<20	125	0.13	<10	217	<10	6	141
41	S07-33362	0.4	6.25	35	680	<5	2.14	<1	17	243	95	4.32	0.86	20	1.74	571	<1	1.90	40	980	34	<5	<20	164	0.17	<10	130	<10	7	127
42	S07-33363	0.6	5.39	30	520	<5	2.81	<1	13	171	87	3.35	0.90	20	1.33	622	<1	1.50	34	810	26	<5	<20	165	0.14	<10	103	<10	5	107
43	S07-33364	6.2	3.99	315	270	<5	0.39	<1	7	41	54	3.53	2.88	<10	0.27	243	7	0.48	25	430	28	75	<20	105	0.29	<10	49	<10	9	53
44	S07-33365	0.4	6.01	15	440	<5	2.62	<1	15	201	99	3.71	0.82	20	1.29	509	2	1.77	37	680	28	<5	<20	153	0.18	<10	174	<10	7	125
45	S07-33366	0.5	6.25	15	480	<5	3.43	<1	19	248	96	4.11	0.95	20	1.74	743	10	1.17	38	940	34	<5	<20	175	0.17	<10	210	<10	7	105
46	S07-33367	0.6	8.34	5	720	<5	3.42	<1	21	121	76	5.85	1.06	<10	2.84	887	<1	1.58	22	810	40	<5	<20	254	0.17	<10	229	<10	7	153
47	S07-33368	1.0	6.93	30	250	<5	3.71	<1	21	197	97	5.75	0.97	10	2.01	876	20	1.38	47	790	36	<5	<20	199	0.16	<10	290	<10	7	150
48	S07-33369	0.6	6.03	25	175	<5	3.62	2	14	260	92	4.27	0.83	20	1.50	770	26	0.76	51	940	26	<5	<20	167	0.15	<10	369	<10	7	236
49	S07-33370	0.7	6.48	25	475	<5	3.24	<1	7	198	59	2.65	0.85	20	1.36	792	9	0.92	22	700	60	<5	<20	171	0.12	<10	120	<10	8	101
50	S07-33371	0.4	5.68	20	235	<5	2.13	1	10	322	60	2.76	0.92	20	1.04	526	8	0.79	30	590	24	<5	<20	124	0.12	<10	122	<10	6	118
51	S07-33372	0.4	6.44	10	285	<5	3.52	<1	11	199	51	2.98	0.97	20	1.64	665	4	0.76	21	610	32	<5	<20	190	0.14	<10	91	<10	9	93
52	S07-33373	0.5	5.67	10	455	<5	3.14	<1	10	248	61	2.76	0.83	20	1.50	706	3	1.42	25	520	26	<5	<20	187	0.14	<10	108	<10	7	81
53	S07-33374	0.8	7.17	20	265	<5	3.62	<1	12	138	58	3.38	0.97	20	1.82	823	<1	0.86	14	680	32	<5	<20	190	0.14	<10	99	<10	10	57
54	S07-33375	0.4	6.21	15	810	<5	2.98	<1	7	265	45	2.38	0.91	10	1.53	685	1	0.44	13	490	52	<5	<20	154	0.13	<10	67	<10	11	45
55	S07-33376	0.6	6.58	15	790	<5	4.19	<1	10	195	57	3.11	0.97	10	1.90	1184	2	0.71	15	730	42	<5	<20	218	0.14	<10	112	<10	10	108
56	S07-33377	0.8	6.97	20	460	<5	4.22	1	16	243	90	5.04	1.14	<10	2.54	952	12	0.74	32	640	72	<5	<20	302	0.15	<10	259	<10	10	174
57	S07-33378	0.6	6.57	30	220	<5	3.57	2	16	353	124	4.48	1.64	20	1.66	860	16	0.81	41	780	44	<5	<20	200	0.17	<10	289	<10	7	228
58	S07-33379	0.4	0.67	<5	85	<5	>10	<1	<1	4	3	0.61	0.10	<10	>10	216	<1	0.06	3	210	4	<5	<20	130	<0.01	<10	3	<10	<1	12
59	S07-33380	1.2	5.96	35	155	<5	2.84	2	12	321	98	3.45	0.94	20	1.45	690	22	0.88	47	670	44	<5	<20	187	0.15	<10	391	<10	6	226
60	S07-33381	1.0	5.83	20	85	<5	2.03	2	15	273	86	3.71	2.84	20	1.12	497	26	0.49	56	850	30	<5	<20	135	0.14	<10	349	<10	6	215
61	S07-33382	1.1	6.17	25	560	<5	3.25	4	10	307	83	3.08	1.08	10	1.45	756	8	0.35	25	780	36	5	<20	180	0.13	<10	110	<10	9	349
62	S07-33383	1.1	6.44	45	410	<5	3.57	<1	10	276	65	3.35	1.12	20	1.80	764	2	0.50	22	580	34	5	<20	191	0.15	<10	95	<10	12	77
63	S07-33384	1.2	7.89	35	775	<5	4.44	<1	11	155	55	3.42	1.21	10	2.08	1137	1	0.91	15	690	40	<5	<20	233	0.17	<10	121	<10	9	74
64	S07-33385	0.4	7.46	25	300	<5	4.44	<1	13	147	57	3.79	1.22	10	2.08	1112	<1	0.91	17	690	38	<5	<20	230	0.15	<10	117	<10	9	64
65	S07-33386	0.4	6.41	15	1150	<5	3.39	<1	8	203	55	2.45	2.76	10	1.68	657	1	0.53	12	600	122	<5	<20	200	0.13	<10	92	<10	9	82
66	S07-33387	0.5	8.10	35	875	<5	3.23	<1	9	202	51	3.00	2.95	20	1.62	683	5	0.72	20	740	42	<5	<20	172	0.16	<10	102	<10	9	80
67	S07-33388	0.6	6.44	30	450	<5	3.69	<1	13	160	59	3.99	2.66	20	1.79	918	<1	0.81	24	590	38	<5	<20	213	0.13	<10	99	<10	9	55
68	S07-33389	0.4	7.06	15	1030	<5	4.21	<1	8	154	51	2.67	2.54	20	1.91	1140	<1	1.23	12	600	34	<5	<20	266	0.13	<10	88	<10	10	58
69	S07-33390	0.8	6.42	35	215	<5	3.40	<1	22	219	63	5.19	2.48	10	1.64	875	8	1.30	36	660	40	<5	<20	243	0.14	<10	148	<10	8	51
70	S07-33391	0.5	6.90	25	390	<5	2.88	<1	13	139	58	3.50	2.79	20	1.59	666	5	1.58	20	580	32	<5	<20	213	0.15	<10	105	<10	10	56

Et #.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	Y	Zn			
71	S07-33392	0.5	6.11	15	840	<5	2.75	<1	9	115	51	2.66	2.16	20	1.39	626	3	1.98	18	550	32	<5	<20	225	0.16	<10	105	<10	9	57
72	S07-33393	0.6	6.66	20	845	<5	3.15	<1	8	153	42	2.81	2.51	20	1.41	849	3	1.74	13	600	30	<5	<20	210	0.15	<10	79	<10	9	62
73	S07-33394	0.4	6.07	35	300	<5	2.00	<1	7	257	34	2.78	2.53	20	1.04	551	11	1.24	16	530	28	<5	<20	160	0.12	<10	92	<10	8	47
74	S07-33395	1.0	6.85	30	150	<5	2.98	<1	13	169	55	4.28	2.80	20	1.26	859	9	1.66	18	1080	36	<5	<20	266	0.17	<10	104	<10	10	80
75	S07-33396	4.2	4.62	160	350	<5	0.51	1	11	42	604	4.87	2.74	10	1.81	402	8	0.24	25	510	112	50	<20	77	0.26	<10	54	<10	11	649
76	S07-33397	0.8	7.38	25	270	<5	3.34	<1	13	147	76	4.15	3.36	20	1.51	827	<1	0.80	15	1020	54	<5	<20	243	0.20	<10	113	<10	10	77
77	S07-33398	0.4	6.69	15	1185	<5	2.56	<1	11	131	52	4.15	3.08	20	1.74	862	<1	0.92	15	1170	40	<5	<20	193	0.21	<10	106	<10	7	96
78	S07-33399	0.5	6.45	40	725	<5	3.44	<1	12	88	58	3.82	2.88	20	1.36	1065	4	0.82	15	950	62	<5	<20	204	0.17	<10	109	<10	8	67
79	S07-33400	0.4	6.83	15	1385	<5	3.06	<1	12	135	80	4.13	3.06	20	1.68	1117	<1	0.66	14	1150	38	<5	<20	194	0.19	<10	117	<10	8	86
80	S07-33401	0.4	6.65	30	910	<5	3.52	<1	15	145	59	5.28	2.87	20	2.07	1311	<1	0.74	19	1130	34	<5	<20	244	0.20	<10	121	<10	9	96
81	S07-33402	<0.2	7.19	15	985	<5	3.89	<1	16	132	30	4.31	3.18	20	1.85	1286	<1	0.52	15	1750	32	<5	<20	277	0.18	<10	126	<10	11	55
82	S07-33403	0.4	7.66	25	490	<5	3.86	<1	15	128	42	4.39	2.91	10	1.64	1105	<1	1.37	17	890	42	<5	<20	305	0.19	<10	162	<10	7	66
83	S07-33404	<0.2	7.58	25	890	<5	3.39	<1	22	184	60	5.53	3.07	10	2.04	1268	<1	1.15	21	910	38	<5	<20	250	0.20	<10	194	<10	6	87
84	S07-33405	0.4	6.87	20	625	<5	3.68	<1	13	174	46	4.14	2.27	10	1.82	1133	<1	2.12	18	880	30	<5	<20	379	0.16	<10	142	<10	8	66
85	S07-33406	0.2	7.96	20	740	<5	3.75	<1	15	119	126	4.09	2.72	10	1.65	1165	<1	2.84	19	1030	40	<5	<20	352	0.22	<10	162	<10	6	46
86	S07-33407	0.2	7.50	30	400	<5	2.93	<1	13	110	56	4.05	1.87	10	1.52	890	<1	3.97	17	950	32	<5	<20	325	0.23	<10	122	<10	6	63
87	S07-33408	0.4	7.23	30	825	<5	3.49	<1	17	131	75	4.65	2.34	10	1.96	1033	<1	2.15	25	800	34	<5	<20	305	0.20	<10	171	<10	6	67
88	S07-33409	0.6	7.66	25	620	<5	3.43	<1	17	106	56	4.84	2.43	10	2.06	1046	<1	2.69	23	830	48	<5	<20	326	0.22	<10	180	<10	6	74
89	S07-33410	0.2	7.69	25	620	<5	3.49	<1	17	95	45	4.93	2.40	10	2.06	1069	<1	2.81	22	850	38	<5	<20	329	0.23	<10	171	<10	6	68
90	S07-33411	0.4	7.84	30	805	<5	3.86	<1	18	85	74	4.95	2.44	10	2.14	1053	<1	2.52	23	860	36	<5	<20	341	0.25	<10	191	<10	7	87
91	S07-33412	0.8	7.05	30	615	<5	3.99	<1	15	113	139	4.85	2.14	10	1.79	1038	4	2.79	23	960	32	<5	<20	342	0.19	<10	184	<10	6	51
92	S07-33413	0.4	7.80	25	715	<5	3.86	<1	15	81	134	4.63	2.43	<10	1.84	1024	<1	3.03	19	830	34	<5	<20	372	0.17	<10	163	<10	5	57
93	S07-33414	0.4	7.84	30	845	<5	3.85	<1	17	66	56	4.93	2.54	10	2.04	1219	<1	1.93	19	980	30	<5	<20	357	0.19	<10	196	<10	6	47
94	S07-33415	0.4	7.36	20	660	<5	3.81	<1	16	73	70	4.30	2.48	<10	1.78	1047	<1	2.27	17	760	28	<5	<20	329	0.18	<10	168	<10	5	63
95	S07-33416	0.2	6.89	15	755	<5	3.40	<1	9	98	56	3.13	2.50	10	1.17	788	<1	1.82	13	730	26	<5	<20	314	0.15	<10	93	<10	6	41
96	S07-33417	0.2	7.61	30	655	<5	3.90	<1	18	90	61	5.03	2.60	10	2.03	1099	<1	2.01	30	940	32	<5	<20	324	0.19	<10	192	<10	5	73
97	S07-33418	0.6	6.00	40	735	<5	2.94	<1	14	124	44	3.49	2.47	10	1.27	692	<1	1.23	18	610	24	<5	<20	266	0.13	<10	109	<10	5	43
98	S07-33419	0.4	6.95	25	635	<5	3.67	<1	17	100	98	4.40	2.24	20	1.63	882	<1	2.50	27	980	30	<5	<20	349	0.17	<10	151	<10	6	64
99	S07-33420	0.5	7.79	15	915	<5	4.51	<1	19	94	55	5.37	2.61	10	2.19	1330	<1	2.01	29	930	30	<5	<20	482	0.19	<10	205	<10	5	72
100	S07-33421	0.6	7.31	10	500	<5	4.44	<1	19	83	186	5.57	2.14	10	1.87	1224	<1	2.60	15	1550	30	<5	<20	481	0.34	<10	215	<10	10	63
101	S07-33422	<0.2	0.76	<5	60	<5	>10	<1	<1	2	4	0.65	0.10	<10	>10	241	<1	0.14	3	190	6	<5	<20	70	<0.01	<10	3	<10	<1	14
102	S07-33423	0.4	7.43	10	720	<5	3.98	<1	17	52	255	6.48	2.79	20	1.88	1141	<1	1.59	13	1870	30	<5	<20	378	0.37	<10	237	<10	14	71
103	S07-33424	1.2	7.98	30	580	<5	4.15	<1	21	65	241	6.37	3.06	20	1.65	1109	<1	1.14	14	1800	34	<5	<20	374	0.29	<10	232	<10	11	79
104	S07-33425	0.8	8.31	10	670	<5	4.07	<1	18	60	199	6.17	3.00	20	1.70	1013	<1	1.38	13	1770	40	<5	<20	373	0.33	<10	233	<10	9	70
105	S07-33426	1.0	7.31	25	655	<5	4.57	<1	21	82	204	6.34	2.34	20	1.82	1049	1	1.92	14	1670	36	<5	<20	433	0.27	<10	199	<10	12	58
106	S07-33427	0.9	7.87	10	650	<5	4.74	<1	18	64	196	6.18	1.06	20	1.63	1050	1	2.74	11	1830	34	<5	<20	486	0.31	<10	204	<10	9	43
107	S07-33428	0.6	7.13	15	530	<5	4.44	<1	17	87	204	6.64	1.12	20	1.71	1049	1	2.73	10	1920	30	<5	<20	409	0.30	<10	205	<10	11	63
108	S07-33429	1.6	6.30	15	300	<5	3.74	<1	13	138	355	5.37	1.09	20	1.48	1072	<1	2.47	10	1470	30	<5	<20	415	0.31	<10	163	<10	11	45
109	S07-33430	0.4	8.19	10	780	<5	4.36	<1	17	98	75	6.04	1.01	10	2.08	1196	<1	2.35	19	1030	28	<5	<20	427	0.23	<10	171	<10	6	65
110	S07-33431	0.6	7.15	15	760	<5	3.85	<1	15	138	113	5.09	1.03	20	1.58	1043	<1	1.50	18	1070	30	<5	<20	304	0.20	<10	162	<10	6	53

Et #.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Li%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
111	S07-33432	0.4	6.70	10	745	<5	3.69	<1	10	251	49	4.45	1.06	20	1.36	1000	<1	1.49	15	1140	26	<5	<20	299	0.21	<10	86	<10	8	53
112	S07-33433	0.8	5.42	135	170	<5	0.25	<1	7	28	31	3.34	4.12	10	0.33	152	3	0.12	13	470	18	35	<20	51	0.34	<10	67	<10	10	39
113	S07-33434	0.4	6.68	20	535	<5	3.59	<1	13	152	40	4.33	1.27	10	1.45	911	<1	1.30	16	820	34	<5	<20	252	0.20	<10	141	<10	5	61
114	S07-33435	0.3	7.24	15	755	<5	3.11	<1	12	180	48	4.66	1.04	10	1.39	898	<1	2.10	16	760	26	<5	<20	278	0.22	<10	116	<10	4	60
115	S07-33436	0.2	7.10	15	670	<5	3.27	<1	15	92	67	4.52	1.02	10	1.39	956	<1	1.56	12	890	36	<5	<20	217	0.24	<10	127	<10	5	52
116	S07-33437	0.2	6.72	10	585	<5	3.36	<1	9	94	48	3.91	1.02	10	1.29	946	<1	1.75	10	790	22	<5	<20	276	0.21	<10	101	<10	6	40
117	S07-33438	0.3	7.36	20	625	<5	3.83	<1	12	134	48	4.67	0.98	10	1.48	1098	<1	1.39	12	830	28	<5	<20	238	0.22	<10	132	<10	5	56
118	S07-33439	0.4	7.31	10	585	<5	3.61	<1	13	75	68	4.45	1.06	20	1.33	883	<1	2.24	12	580	28	<5	<20	255	0.22	<10	110	<10	5	55
119	S07-33440	0.4	8.22	25	670	<5	3.12	<1	18	106	90	5.43	1.07	10	1.68	1086	<1	2.10	17	810	34	<5	<20	272	0.26	<10	164	<10	5	71
120	S07-33441	0.2	5.98	15	625	<5	2.65	<1	6	174	41	3.02	1.02	20	1.04	715	<1	0.89	8	600	30	<5	<20	221	0.16	<10	54	<10	7	77
121	S07-33442	0.5	6.63	10	505	<5	2.96	2	11	219	55	3.84	1.08	10	1.23	793	<1	2.24	14	720	118	<5	<20	316	0.20	<10	114	<10	6	220
122	S07-33443	0.5	7.56	10	660	<5	3.04	<1	15	119	94	5.08	1.07	10	1.57	1010	<1	3.13	13	830	34	<5	<20	423	0.20	<10	150	<10	5	85
123	S07-33444	0.5	8.88	10	615	<5	3.51	<1	17	94	107	6.11	1.05	10	1.72	1136	<1	3.45	16	900	30	<5	<20	474	0.25	<10	160	<10	5	72
124	S07-33445	0.2	6.59	15	390	<5	3.94	<1	10	138	124	3.58	1.08	<10	1.53	1057	<1	3.79	9	640	30	<5	<20	612	0.18	<10	118	<10	5	95
125	S07-33446	1.0	7.71	15	695	<5	3.35	<1	21	117	73	5.79	1.19	<10	1.95	1050	<1	2.42	19	820	234	<5	<20	360	0.22	<10	194	<10	4	91
126	S07-33447	0.6	7.29	25	760	<5	3.73	<1	23	175	37	6.18	1.13	<10	2.43	1047	<1	1.23	36	850	84	<5	<20	268	0.23	<10	196	<10	5	60
127	S07-33448	1.0	7.39	25	390	<5	2.55	<1	11	120	58	4.30	1.20	10	1.38	689	<1	3.52	14	790	26	<5	<20	268	0.24	<10	110	<10	7	33
128	S07-33449	0.4	7.59	30	590	<5	2.98	<1	19	114	102	5.50	1.02	10	2.07	843	<1	2.84	25	890	26	<5	<20	253	0.23	<10	144	<10	6	48
129	S07-33450	<0.2	8.49	20	640	<5	3.32	<1	19	108	102	5.93	1.01	10	2.11	943	<1	2.99	26	990	28	<5	<20	263	0.27	<10	158	<10	6	50
130	S07-33451	<0.2	7.17	45	985	<5	5.01	<1	26	124	56	6.43	1.06	<10	3.18	1144	<1	1.63	51	850	22	<5	<20	355	0.20	<10	213	<10	7	48
131	S07-33452	<0.2	7.59	35	725	<5	5.56	<1	29	111	78	7.20	1.09	<10	3.46	1219	<1	1.46	54	890	26	<5	<20	346	0.19	<10	220	<10	6	51
132	S07-33453	0.6	7.54	20	855	<5	3.66	<1	26	93	85	6.77	1.13	10	3.24	1037	<1	1.96	47	870	30	<5	<20	370	0.23	<10	232	<10	6	59
133	S07-33454	0.5	8.10	25	705	<5	4.40	<1	26	105	60	6.74	1.10	10	2.79	1157	<1	2.31	40	1030	62	<5	<20	370	0.25	<10	245	<10	7	63
134	S07-33455	0.2	7.64	25	980	<5	3.85	<1	21	132	65	6.48	0.99	10	2.47	983	<1	2.90	33	1050	26	<5	<20	355	0.24	<10	229	<10	7	48
135	S07-33456	0.5	6.96	25	940	<5	3.54	<1	20	57	114	5.63	1.10	<10	2.33	914	<1	2.78	23	770	28	<5	<20	341	0.23	<10	268	<10	6	47
136	S07-33457	0.6	7.91	30	885	<5	2.93	<1	20	106	142	5.65	1.05	10	2.28	760	<1	2.95	25	830	42	<5	<20	335	0.25	<10	251	<10	7	55
137	S07-33458	0.3	7.17	20	415	<5	3.35	<1	13	85	94	4.18	1.05	20	1.66	716	<1	4.52	15	1260	28	<5	<20	399	0.23	<10	150	<10	9	67
138	S07-33459	<0.2	0.41	<5	180	<5	>10	<1	<1	3	3	0.55	0.20	<10	>10	169	<1	0.07	2	150	6	<5	<20	433	<0.01	<10	4	<10	1	10
139	S07-33460	0.4	7.81	20	880	<5	3.21	<1	14	131	65	5.02	1.05	10	1.74	864	<1	3.53	17	880	32	<5	<20	422	0.22	<10	139	<10	5	37
140	S07-33461	0.2	7.11	20	670	<5	3.40	<1	12	120	65	4.43	1.14	10	1.68	865	<1	3.90	14	800	26	<5	<20	463	0.22	<10	138	<10	6	44
141	S07-33462	0.6	8.18	25	675	<5	2.99	<1	17	99	79	5.70	1.09	10	2.02	938	<1	4.59	25	940	30	<5	<20	397	0.26	<10	180	<10	6	57
142	S07-33463	0.6	8.27	30	730	<5	3.84	<1	20	129	147	6.07	1.17	20	2.15	910	<1	3.52	29	1420	46	<5	<20	385	0.31	<10	234	<10	7	66
143	S07-33464	0.2	7.13	20	1530	<5	1.99	<1	14	194	49	4.24	1.31	20	1.91	791	<1	1.07	27	900	78	<5	<20	202	0.21	<10	156	<10	6	120
144	S07-33465	0.2	6.91	30	2190	<5	2.43	<1	12	153	10	3.56	1.16	20	2.07	1113	<1	0.36	27	500	26	<5	<20	210	0.15	<10	98	<10	7	49
145	S07-33466	<0.2	7.72	25	2290	<5	2.49	<1	14	132	12	3.73	1.29	20	1.98	910	1	0.36	29	560	28	<5	<20	214	0.16	<10	103	<10	8	87
146	S07-33467	0.2	7.29	45	485	<5	2.38	<1	13	262	24	4.39	1.97	20	2.15	927	<1	0.39	35	1140	28	<5	<20	208	0.15	<10	88	<10	9	60
147	S07-33468	1.0	5.66	35	200	<5	4.87	<1	14	188	303	4.88	1.97	20	2.20	1874	<1	0.28	39	790	40	<5	<20	357	0.19	<10	114	<10	8	98
148	S07-33469	6.6	3.95	195	115	<5	0.39	<1	6	38	55	3.54	2.97	<10	0.25	217	6	0.58	20	420	26	65	<20	99	0.27	<10	51	<10	9	41
149	S07-33470	0.2	7.10	35	710	<5	1.19	<1	19	172	106	5.33	1.74	20	2.07	692	1	0.28	59	670	32	<5	<20	116	0.19	<10	168	<10	5	78
150	S07-33471	0.6	5.32	35	710	<5	1.80	<1	14	251	101	4.14	1.83	10	1.63	723	<1	0.18	42	580	28	<5	<20	153	0.15	<10	115	<10	6	92

Et #.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
151	S07-33472	0.6	5.55	50	1000	<5	1.58	<1	13	346	58	4.64	1.83	20	1.79	710	2	0.22	83	480	32	5	<20	146	0.12	<10	79	<10	7	106
152	S07-33473	0.6	5.29	120	1460	<5	1.71	1	14	105	130	2.98	1.94	20	1.36	646	7	0.35	107	540	28	<5	<20	160	0.11	<10	89	<10	5	163
153	S07-33474	0.4	5.88	55	1400	<5	1.52	1	11	74	138	3.10	1.88	20	1.33	653	7	0.23	94	510	28	<5	<20	137	0.12	<10	84	<10	5	176
154	S07-33475	1.0	4.47	105	340	<5	2.04	10	10	142	139	3.72	1.88	20	1.51	1347	106	0.14	103	960	42	<5	<20	187	0.14	<10	803	<10	7	1090
155	S07-33476	1.0	5.35	75	470	<5	2.47	2	20	92	123	3.86	1.94	20	1.63	2353	11	0.17	107	440	24	<5	<20	221	0.14	<10	188	<10	5	194
156	S07-33477	0.6	6.02	50	1050	<5	1.75	<1	20	87	147	3.94	2.03	20	1.55	2296	1	0.40	120	450	26	<5	<20	173	0.16	<10	101	<10	4	138
157	S07-33478	0.2	5.33	50	1015	<5	1.78	<1	18	82	181	3.64	1.89	30	1.61	2450	1	0.32	172	450	26	<5	<20	178	0.14	<10	97	<10	4	160
158	S07-33479	0.8	5.52	125	1000	<5	2.26	1	21	77	255	3.76	1.72	20	1.87	2899	<1	0.26	187	440	26	<5	<20	216	0.14	<10	86	<10	5	227
159	S07-33480	0.7	5.87	100	1010	<5	1.73	<1	14	79	107	3.59	2.27	30	1.94	2759	<1	0.51	180	500	28	<5	<20	191	0.16	<10	91	<10	5	119
160	S07-33481	0.6	6.40	150	965	<5	2.03	<1	15	77	148	3.94	2.07	20	1.80	3063	<1	0.49	199	540	30	<5	<20	187	0.17	<10	87	<10	5	146
161	S07-33482	0.3	5.01	95	1010	<5	1.78	<1	10	72	50	2.78	2.36	20	1.65	2310	<1	0.45	87	420	24	<5	<20	189	0.13	<10	75	<10	4	79
162	S07-33483	1.2	4.78	65	560	<5	1.99	<1	12	79	88	3.51	1.97	20	1.69	2696	<1	0.30	136	400	30	<5	<20	196	0.13	<10	77	<10	4	117
163	S07-33484	0.8	4.84	105	795	<5	1.68	<1	14	83	100	3.22	2.22	20	1.70	2472	<1	0.38	135	420	26	<5	<20	164	0.15	<10	74	<10	4	116
164	S07-33485	2.6	4.22	150	495	<5	1.73	1	12	93	74	3.38	2.06	20	1.62	2363	<1	0.24	137	450	46	<5	<20	177	0.11	<10	71	<10	4	161
165	S07-33486	1.0	5.41	100	1130	<5	1.90	<1	15	74	54	3.13	2.19	20	1.54	2627	<1	0.21	124	410	28	<5	<20	167	0.14	<10	73	<10	4	86
166	S07-33487	4.8	4.36	160	270	<5	0.50	2	10	38	603	5.27	2.46	10	1.64	344	6	0.23	21	490	84	45	<20	68	0.23	<10	47	<10	10	663
167	S07-33488	0.3	4.27	145	845	<5	2.21	<1	12	90	84	2.96	2.13	20	1.81	2965	<1	0.28	121	350	24	<5	<20	222	0.09	<10	66	<10	4	87
168	S07-33489	0.8	5.17	185	845	<5	2.03	<1	14	78	74	3.47	2.36	30	1.85	3008	<1	0.62	161	480	28	<5	<20	203	0.14	<10	79	<10	5	103
169	S07-33490	0.6	4.66	65	805	<5	2.45	<1	10	80	139	2.58	2.23	20	1.49	3093	<1	0.49	94	510	24	<5	<20	246	0.11	<10	68	<10	4	73
170	S07-33491	1.0	4.61	70	655	<5	2.13	1	12	84	254	3.09	1.15	20	1.65	2985	1	0.45	144	410	38	<5	<20	211	0.13	<10	70	<10	4	184
171	S07-33492	0.6	4.54	65	720	<5	1.99	<1	10	80	76	2.77	1.08	20	1.61	2712	<1	0.35	108	330	22	<5	<20	192	0.12	<10	69	<10	4	97
172	S07-33493	1.6	4.40	60	420	<5	1.99	<1	10	81	94	3.58	1.25	20	1.72	2650	<1	0.19	89	330	50	<5	<20	194	0.10	<10	66	<10	4	103
173	S07-33494	0.2	4.29	45	580	<5	2.08	<1	9	78	43	2.09	1.14	20	1.16	1452	<1	0.50	64	360	22	<5	<20	206	0.10	<10	54	<10	4	42

QC DATA:


Repeat:


1	S07-33322	0.6	5.24	90	775	<5	1.18	<1	14	317	33	2.57	1.30	10	1.34	1403	3	0.22	100	520	32	<5	<20	99	0.13	<10	59	<10	7	104
10	S07-33331	2.8	5.12	35	170	<5	2.54	3	16	330	78	5.23	2.18	20	1.37	705	40	0.16	87	950	78	15	<20	109	0.11	<10	260	<10	7	278
19	S07-33340	0.4	5.93	40	140	<5	3.11	2	12	390	58	3.62	0.97	20	1.56	749	15	0.47	43	990	30	<5	<20	154	0.13	<10	158	<10	9	150
36	S07-33357	0.3	6.15	10	1890	<5	1.47	<1	9	231	43	2.84	0.81	20	1.53	464	4	1.25	20	520	28	<5	<20	115	0.14	<10	89	<10	7	87
45	S07-33366	0.4	6.33	15	495	<5	3.49	<1	19	250	94	4.13	0.97	20	1.76	758	10	1.17	38	970	32	<5	<20	178	0.16	<10	218	<10	7	106
54	S07-33375	0.4	5.94	15	800	<5	2.96	<1	7	249	45	2.30	0.95	10	1.52	665	<1	0.46	12	480	54	<5	<20	154	0.12	<10	67	<10	9	43
71	S07-33392	0.5	6.04	25	790	<5	2.88	<1	8	122	49	2.70	2.10	20	1.36	623	3	1.93	18	570	38	<5	<20	218	0.14	<10	103	<10	10	61
80	S07-33401	0.4	6.83	20	915	<5	3.65	<1	15	141	56	5.28	2.68	20	2.03	1310	<1	0.75	18	1130	38	<5	<20	237	0.22	<10	119	<10	9	93
89	S07-33410	0.2	7.86	20	605	<5	3.50	<1	18	94	45	4.91	2.61	10	2.11	1085	<1	2.81	24	860	36	<5	<20	336	0.24	<10	187	<10	5	64
106	S07-33427	1.2	7.97	15	655	<5	4.65	<1	18	69	204	6.45	1.06	20	1.60	1041	<1	2.93	11	1740	30	<5	<20	467	0.29	<10	199	<10	9	40
115	S07-33436	0.2	6.97	20	695	<5	3.04	<1	15	97	67	4.55	1.09	10	1.37	917	<1	1.61	13	840	34	<5	<20	212	0.23	<10	122	<10	5	46
124	S07-33445	0.3	7.03	20	425	<5	3.68	<1	9	138	127	3.60	1.00	<10	1.52	1148	<1	3.72	9	710	32	<5	<20	584	0.20	<10	116	<10	5	98
141	S07-33462	0.4	7.85	30	695	<5	3.19	<1	18	106	80	5.49	1.28	10	2.08	917	<1	4.59	24	930	30	<5	<20	410	0.26	<10	173	<10	8	56
150	S07-33471	0.6	5.63	30	685	<5	1.98	<1	16	236	100	4.42	1.76	10	1.60	754	<1	0.17	44	590	34	<5	<20	145	0.16	<10	114	<10	5	93
159	S07-33480	0.6	5.89	105	960	<5	1.80	<1	16	81	117	3.56	2.32	30	1.83	2682	<1	0.51	181	490	26	<5	<20	176	0.15	<10	88	<10	5	108

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
Resplit:																															
1	S07-33322	0.6	5.27	100	615	<5	1.28	<1	15	308	34	2.70	0.95	10	1.41	1406	4	0.22	106	520	30	5	<20	97	0.14	<10	65	<10	12	102	
36	S07-33357	0.3	6.19	10	2015	<5	1.49	<1	9	234	40	2.96	2.37	20	1.67	443	4	1.22	19	500	30	<5	<20	121	0.12	<10	88	<10	7	82	
71	S07-33392	0.6	6.33	20	860	<5	2.87	<1	8	114	56	2.79	2.16	20	1.37	601	3	1.97	19	540	34	<5	<20	220	0.15	<10	104	<10	9	60	
106	S07-33427	1.0	7.60	15	670	<5	4.74	<1	18	60	208	6.19	1.13	10	1.58	999	1	2.82	11	1590	28	<5	<20	456	0.29	<10	197	<10	10	43	
141	S07-33462	0.5	7.65	20	635	<5	2.73	<1	18	102	86	5.17	1.10	10	1.89	893	<1	4.24	22	877	28	<5	<20	366	0.26	<10	166	<10	5	58	
Standard:																															
Stsd3		0.5	5.76	25	1410	<5	2.48	<1	15	63	40	4.21	1.36	40	1.26	2648	5	1.11	37	1640	63	<5	<20	273	0.34	<10	116	<10	30	196	
Stsd3		0.4	5.34	20	1420	<5	2.34	<1	15	65	41	3.97	1.32	40	1.25	2566	5	1.12	35	1640	62	<5	<20	268	0.32	<10	116	<10	30	200	
Stsd3		0.4	5.68	25	1430	<5	2.46	<1	15	63	42	4.15	1.31	40	1.33	2577	5	1.15	35	1620	58	<5	<20	264	0.34	<10	116	<10	30	198	
Stsd3		0.5	5.58	20	1290	<5	2.29	<1	14	57	39	4.17	1.29	40	1.35	2539	6	1.14	28	1760	52	<5	<20	244	0.30	<10	111	<10	29	209	
Stsd3		0.5	5.70	20	1345	<5	2.38	<1	13	52	37	4.10	1.34	30	1.29	2516	6	1.12	28	1760	52	<5	<20	275	0.28	<10	100	<10	26	207	

ICP: 4 ACID DIGEST/ICP-FINISH
AG: 4 ACID DIGEST/AA-FINISH

JJ/nw
df/td2212as/td2212bs
XLS/07


ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2270

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

3-Mar-08


Attention: Bob Singh

No. of samples received: 88
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-136
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-33593	0.80	0.023
2	S07-33594	0.40	0.012
3	S07-33595	<0.03	<0.001
4	S07-33596	0.16	0.005
5	S07-33597	0.27	0.008
6	S07-33598	0.14	0.004
7	S07-33599	0.22	0.006
8	S07-33600	0.32	0.009
9	S07-33601	0.51	0.015
10	S07-33602	1.02	0.030
11	S07-33603	0.08	0.002
12	S07-33604	<0.03	<0.001
13	S07-33605	<0.03	<0.001
14	S07-33606	<0.03	<0.001
15	S07-33607	0.04	0.001
16	S07-33608	0.08	0.002
17	S07-33609	<0.03	<0.001
18	S07-33610	<0.03	<0.001
19	S07-33611	0.13	0.004
20	S07-33612	0.92	0.027
21	S07-33613	0.79	0.023
22	S07-33614	0.53	0.015
23	S07-33615	0.91	0.026
24	S07-33616	2.98	0.087
25	S07-33617	0.09	0.003
26	S07-33618	0.06	0.002
27	S07-33619	<0.03	<0.001
28	S07-33620	<0.03	<0.001
29	S07-33621	<0.03	<0.001
30	S07-33622	<0.03	<0.001


* = 30g FA


ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
31	S07-33623	<0.03	<0.001
32	S07-33624	<0.03	<0.001
33	S07-33625	<0.03	<0.001
34	S07-33626	0.22	0.006
35	S07-33627	<0.03	<0.001
36	S07-33628	<0.03	<0.001
37	S07-33629	0.06	0.002
38	S07-33630	0.35	0.010
39	S07-33631	<0.03	<0.001
40	S07-33632	0.43	0.013
41	S07-33633	0.06	0.002
42	S07-33634	0.10	0.003
43	S07-33635	5.46	0.159
44	S07-33636	0.39	0.011
45	S07-33637	0.12	0.003
46	S07-33638	<0.03	<0.001
47	S07-33639	<0.03	<0.001
48	S07-33640	<0.03	<0.001
49	S07-33641	0.11	0.003
50	S07-33642	<0.03	<0.001
51	S07-33643	<0.03	<0.001
52	S07-33644	0.09	0.003
53	S07-33645	<0.03	<0.001
54	S07-33646	0.05	0.002
55	S07-33647	0.05	0.002
56	S07-33648	<0.03	<0.001
57	S07-33649	<0.03	<0.001
58	S07-33650	0.06	0.002
59	S07-33651	<0.03	<0.001
60	S07-33652	0.03	0.001
61	S07-33653	0.04	0.001
62	S07-33654	0.03	0.001
63	S07-33655	0.04	0.001
64	S07-33656	0.03	0.001
65	S07-33657	0.03	0.001
66	S07-33658	0.07	0.002
67	S07-33659	0.06	0.002
68	S07-33660	<0.03	<0.001
69	S07-33661	0.04	0.001
70	S07-33662	0.03	0.001
71	S07-33663	<0.03	<0.001
72	S07-33664	6.65	0.194

* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
73	S07-33665	0.20	0.006
74	S07-33666	0.11	0.003
75	S07-33667	<0.03	<0.001
76	S07-33668	0.78	0.023
77	S07-33669	0.05	0.002
78	S07-33670	0.06	0.002
79	S07-33671	0.04	0.001
80	S07-33672	<0.03	<0.001
81	S07-33673	0.17	0.005
82	S07-33674	<0.03	<0.001
83	S07-33675	0.03	0.001
84	S07-33676	0.08	0.002
85	S07-33677	0.03	0.001
86	S07-33678	<0.03	<0.001
87	S07-33679	0.04	0.001
88	S07-33680	<0.03	<0.001

QC DATA:

Resplit:

1	S07-33593	0.41	0.012
36	S07-33628	0.03	0.001
71	S07-33663	<0.03	<0.001


Standard:

OXI54	1.80	0.052
OXI54	1.83	0.053
OXI54	1.89	0.055
OXI54	1.87	0.055
OXI54	1.89	0.055
OXI54	1.86	0.054
OXI54	1.83	0.053

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw
XLS/07



ECO TECH LABORATORY LTD.

Jutta Vealouse
B.C. Certified Assayer

3-Mar-08

CO TECH LABORATORY LTD.

0041 Dallas Drive
 AMLOOPS, B.C.
 2C 6T4

Phone: 250-573-5700
 Fax: 250-573-4557

ICP CERTIFICATE OF ANALYSIS AN 2007-2270

Skygold Ventures
 615 - 800 W. Pender Street
 Vancouver, BC
 V6B 2V6

No. of samples received: 88

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-136

Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-33593	1.0	6.64	60	250	<5	4.09	<1	19	271	130	5.57	1.91	10	1.42	1059	1	2.33	15	1550	32	<5	<20	562	0.22	<10	178	<10	7	41
2	S07-33594	0.6	8.46	45	590	<5	4.28	<1	20	65	180	6.51	2.67	10	1.82	1288	<1	2.48	13	2100	42	<5	<20	525	0.25	<10	213	<10	9	62
3	S07-33595	<0.2	0.11	<5	20	<5	>10	<1	<1	3	2	0.56	0.15	<10	>10	203	<1	0.02	2	170	2	<5	<20	49	<0.01	<10	3	<10	<1	14
4	S07-33596	0.8	7.98	20	510	<5	4.31	<1	19	163	200	6.40	2.60	20	1.74	1210	1	1.80	13	2030	38	<5	<20	333	0.24	<10	206	<10	9	67
5	S07-33597	1.0	7.16	15	475	<5	3.43	<1	20	132	280	6.56	2.42	20	1.87	1052	2	1.46	12	1990	30	<5	<20	232	0.22	<10	223	<10	10	84
6	S07-33598	1.2	7.26	25	545	<5	3.82	<1	19	141	202	6.46	2.19	20	1.88	1346	1	1.67	12	1970	30	<5	<20	330	0.24	<10	219	<10	10	62
7	S07-33599	0.6	6.27	25	505	<5	3.47	<1	14	122	116	4.68	1.71	20	1.63	1153	1	2.52	12	1370	30	<5	<20	542	0.22	<10	165	<10	8	92
8	S07-33600	0.4	7.68	20	705	<5	3.56	<1	13	95	52	5.24	2.06	20	1.72	1223	<1	2.52	13	1250	44	<5	<20	491	0.24	<10	147	<10	7	70
9	S07-33601	2.4	6.83	40	645	<5	3.11	<1	14	145	816	4.45	2.35	10	1.53	1050	1	1.83	18	990	46	<5	<20	439	0.19	<10	146	<10	6	62
10	S07-33602	0.8	7.11	40	800	<5	3.14	<1	12	109	57	4.40	2.55	10	1.52	1081	1	1.81	16	1220	342	<5	<20	346	0.20	<10	127	<10	7	87
11	S07-33603	0.4	7.93	40	755	<5	2.75	<1	14	132	108	4.51	2.49	10	1.49	1130	<1	2.19	17	1030	34	<5	<20	292	0.21	<10	119	<10	5	72
12	S07-33604	0.2	7.75	30	675	<5	3.23	<1	16	139	48	4.88	2.47	<10	1.74	1221	<1	2.35	20	980	32	<5	<20	333	0.21	<10	148	<10	5	86
13	S07-33605	0.2	6.98	10	595	<5	3.82	<1	10	169	38	3.68	2.34	10	1.28	1026	<1	1.60	12	680	26	<5	<20	292	0.18	<10	97	<10	6	56
14	S07-33606	<0.2	7.61	15	575	<5	4.30	<1	11	54	33	3.91	2.41	10	1.28	1128	<1	1.68	12	820	32	<5	<20	285	0.20	<10	97	<10	6	67
15	S07-33607	0.2	7.85	20	665	<5	3.21	<1	13	53	63	4.05	2.34	10	1.45	991	2	2.00	14	620	30	<5	<20	279	0.19	<10	129	<10	4	60
16	S07-33608	0.2	8.79	15	685	<5	3.41	<1	13	41	56	4.77	2.69	10	1.64	1185	<1	2.02	17	810	34	<5	<20	260	0.21	<10	140	<10	5	52
17	S07-33609	0.2	8.05	15	390	<5	3.84	<1	18	33	58	5.14	1.62	<10	1.93	1333	<1	2.85	16	780	32	<5	<20	520	0.21	<10	169	<10	4	63
18	S07-33610	0.2	7.74	20	575	<5	3.14	<1	15	40	67	4.70	2.22	<10	1.95	1098	1	2.54	17	730	32	<5	<20	520	0.18	<10	182	<10	3	64
19	S07-33611	0.4	6.42	15	545	<5	2.03	<1	9	112	46	2.88	1.84	10	0.96	698	<1	2.15	12	600	30	<5	<20	294	0.15	<10	78	<10	5	47
20	S07-33612	0.4	8.34	30	645	<5	3.55	<1	16	62	82	4.52	2.32	10	1.64	1097	<1	2.22	16	900	32	<5	<20	334	0.22	<10	150	<10	5	52
21	S07-33613	0.8	7.52	25	465	<5	3.72	<1	18	77	65	4.67	2.05	<10	1.75	1211	<1	2.11	15	880	32	<5	<20	294	0.22	<10	144	<10	7	55
22	S07-33614	0.2	7.63	30	630	<5	4.09	<1	17	47	49	5.03	1.97	<10	1.74	1307	<1	2.91	16	840	30	<5	<20	515	0.20	<10	164	<10	5	58
23	S07-33615	0.4	7.64	25	700	<5	4.04	<1	23	97	35	5.40	2.38	<10	2.33	1331	<1	2.52	31	860	40	<5	<20	559	0.18	<10	217	<10	5	88
24	S07-33616	1.4	7.04	15	650	<5	4.99	<1	20	133	29	5.37	2.02	<10	2.89	1371	<1	2.00	37	900	42	<5	<20	648	0.15	<10	196	<10	6	67
25	S07-33617	0.4	7.25	25	620	<5	4.37	<1	23	110	33	5.19	2.07	<10	2.73	1219	<1	2.48	37	880	32	<5	<20	532	0.17	<10	200	<10	6	58

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
26	S07-33618	0.8	7.50	15	470	<5	4.03	<1	19	86	97	4.80	1.75	10	2.45	1081	<1	3.11	28	920	32	<5	<20	518	0.20	<10	158	<10	8	53
27	S07-33619	0.2	7.27	20	905	<5	4.65	<1	27	124	83	5.47	2.38	<10	3.15	1203	<1	1.83	44	1060	30	<5	<20	418	0.16	<10	216	<10	6	60
28	S07-33620	0.4	8.06	15	800	<5	4.81	<1	25	71	97	5.72	2.12	<10	2.94	1278	<1	1.73	27	930	34	<5	<20	380	0.18	<10	234	<10	6	52
29	S07-33621	0.2	8.06	15	530	<5	4.02	<1	20	70	74	5.78	1.46	<10	2.53	1178	<1	2.95	25	1010	32	<5	<20	455	0.21	<10	223	<10	6	65
30	S07-33622	0.2	7.90	15	475	<5	3.50	<1	19	66	97	4.51	0.91	<10	2.01	955	<1	3.60	21	930	32	<5	<20	349	0.27	<10	199	<10	6	56
31	S07-33623	<0.2	0.08	<5	25	<5	>10	<1	<1	<1	2	0.56	0.03	<10	>10	205	<1	0.03	2	180	4	<5	<20	48	<0.01	<10	4	<10	<1	12
32	S07-33624	0.2	7.92	10	660	<5	3.72	<1	23	95	92	5.92	1.19	10	2.76	1126	<1	3.31	42	1450	34	<5	<20	358	0.25	<10	221	<10	8	71
33	S07-33625	0.2	6.58	30	1000	<5	4.10	<1	29	209	8	5.70	2.00	10	3.65	1282	<1	1.47	81	1180	30	<5	<20	368	0.15	<10	215	<10	7	77
34	S07-33626	0.6	8.35	20	855	<5	4.10	<1	28	118	101	6.20	1.73	10	2.71	1159	<1	2.97	44	1350	140	<5	<20	352	0.26	<10	237	<10	7	72
35	S07-33627	0.2	7.78	15	325	<5	3.36	<1	25	77	93	5.60	0.79	10	2.47	1067	<1	3.80	33	1120	32	<5	<20	329	0.32	<10	226	<10	7	66
36	S07-33628	0.4	7.70	15	905	<5	4.09	<1	26	101	86	5.88	1.59	<10	3.06	1290	<1	2.76	38	1100	34	<5	<20	408	0.24	<10	225	<10	7	61
37	S07-33629	0.4	7.46	15	535	<5	3.66	<1	22	129	61	5.55	1.66	10	2.86	1231	<1	2.95	35	1100	36	<5	<20	414	0.24	<10	228	<10	7	58
38	S07-33630	0.6	7.30	15	560	<5	4.09	<1	23	159	85	5.91	1.69	10	3.33	1255	<1	2.59	54	1220	74	<5	<20	415	0.18	<10	189	<10	7	63
39	S07-33631	0.2	7.32	25	810	<5	3.91	<1	35	222	135	6.32	1.85	<10	3.65	1144	<1	2.29	86	1200	36	<5	<20	395	0.14	<10	313	<10	6	70
40	S07-33632	0.9	5.81	115	265	<5	0.27	<1	8	25	30	3.23	4.18	10	0.35	172	3	0.11	16	520	22	40	<20	54	0.37	<10	67	<10	10	44
41	S07-33633	0.4	5.80	25	700	<5	6.71	<1	25	316	50	5.64	1.86	<10	3.93	1349	<1	1.80	91	1020	50	<5	<20	646	0.08	<10	233	<10	6	53
42	S07-33634	0.6	6.84	55	920	<5	6.33	<1	36	389	32	5.80	2.30	<10	4.18	1521	<1	1.12	115	1110	44	5	<20	553	0.10	<10	276	<10	7	53
43	S07-33635	0.6	6.57	60	1055	<5	3.12	<1	29	367	63	5.71	2.14	<10	3.30	1250	<1	1.14	85	1080	44	5	<20	350	0.14	<10	221	<10	6	71
44	S07-33636	0.6	4.08	20	675	<5	1.36	<1	9	416	44	2.07	1.84	20	0.93	602	4	0.10	75	490	28	5	<20	140	0.11	<10	89	<10	4	132
45	S07-33637	0.8	4.00	25	280	<5	1.67	1	15	268	80	3.10	1.71	20	1.17	756	6	0.09	119	520	26	<5	<20	135	0.10	<10	80	<10	4	200
46	S07-33638	0.6	4.87	25	1265	<5	1.27	1	14	193	121	3.49	2.21	20	1.56	711	4	0.16	110	830	38	<5	<20	117	0.14	<10	96	<10	6	207
47	S07-33639	0.6	4.86	20	1270	<5	1.45	<1	11	221	128	2.82	2.13	20	1.38	718	5	0.13	103	760	50	<5	<20	125	0.14	<10	94	<10	6	185
48	S07-33640	0.8	4.98	25	1255	<5	2.46	<1	14	209	136	2.95	1.84	20	1.47	908	<1	0.13	90	620	32	<5	<20	186	0.14	<10	95	<10	5	135
49	S07-33641	0.4	4.88	20	1320	<5	2.11	<1	11	223	55	2.80	1.85	20	1.46	802	3	0.14	77	530	30	<5	<20	165	0.13	<10	74	<10	5	143
50	S07-33642	0.8	4.93	20	1235	<5	1.66	<1	8	185	116	2.96	1.75	20	1.35	746	4	0.15	68	620	36	<5	<20	139	0.13	<10	102	<10	5	160
51	S07-33643	0.4	4.79	10	970	<5	4.00	<1	13	223	40	2.89	1.60	30	1.66	2697	<1	0.75	29	1320	26	<5	<20	306	0.12	<10	100	<10	8	75
52	S07-33644	0.4	4.18	15	705	<5	3.66	<1	10	293	102	2.72	1.63	10	1.53	1576	<1	0.30	44	970	28	5	<20	299	0.11	<10	80	<10	7	73
53	S07-33645	0.6	6.40	30	1070	<5	3.73	<1	17	171	84	3.62	2.12	20	1.95	1689	<1	0.43	70	740	38	<5	<20	278	0.20	<10	123	<10	7	125
54	S07-33646	0.8	6.02	45	265	<5	2.57	<1	25	205	66	3.66	2.12	20	1.58	2228	2	0.24	123	560	38	<5	<20	225	0.18	<10	113	<10	5	172
55	S07-33647	0.8	6.04	35	1245	<5	1.42	<1	16	197	91	3.18	2.33	20	1.69	2501	<1	0.28	122	490	38	<5	<20	150	0.20	<10	99	<10	5	170
56	S07-33648	1.0	5.91	35	1125	<5	1.38	<1	16	195	197	3.27	2.08	20	1.81	2863	<1	0.40	177	500	40	<5	<20	153	0.20	<10	97	<10	5	172
57	S07-33649	0.8	5.82	30	1100	<5	2.01	<1	12	174	80	2.80	2.01	30	1.93	3324	<1	0.46	139	580	34	<5	<20	219	0.19	<10	95	<10	5	154
58	S07-33650	1.0	5.69	35	1080	<5	1.61	<1	15	143	123	3.29	2.27	30	1.96	2883	<1	0.53	160	500	38	<5	<20	188	0.17	<10	100	<10	5	195
59	S07-33651	0.6	4.48	30	780	<5	2.79	<1	11	219	82	3.00	1.93	20	2.08	4638	<1	0.35	97	500	30	<5	<20	302	0.17	<10	75	<10	5	100
60	S07-33652	0.8	6.43	40	1155	<5	1.60	<1	15	149	152	2.73	2.52	30	1.83	2822	1	0.59	180	550	40	<5	<20	180	0.21	<10	107	<10	5	200
61	S07-33653	0.8	4.43	25	755	<5	2.46	<1	17	172	115	3.03	1.79	20	1.80	3695	<1	0.28	135	410	34	<5	<20	232	0.16	<10	74	<10	4	150
62	S07-33654	0.8	4.48	50	760	<5	2.00	<1	16	255	106	3.13	1.94	20	1.90	3285	<1	0.25	204	520	40	<5	<20	214	0.15	<10	83	<10	5	161
63	S07-33655	1.0	5.13	35	870	<5	1.76	<1	13	182	108	2.59	2.21	20	1.82	2804	<1	0.35	141	500	36	<5	<20	198	0.18	<10	85	<10	5	144
64	S07-33656	1.0	5.14	55	715	<5	2.00	<1	19	193	92	3.14	1.77	20	1.76	3280	<1	0.37	210	580	36	<5	<20	221	0.17	<10	84	<10	5	182
65	S07-33657	1.2	6.21	40	1005	<5	1.68	<1	18	169	171	3.05	2.19	20	1.84	2978	<1	0.39	202	540	42	<5	<20	181	0.21	<10	94	<10	5	149

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
66	S07-33658	1.0	4.53	55	745	<5	2.07	<1	14	187	67	2.62	1.50	20	1.66	3129	<1	0.30	95	430	38	<5	<20	217	0.15	<10	73	<10	4	108
67	S07-33659	1.0	4.88	25	810	<5	1.71	<1	14	148	47	2.53	1.73	20	1.66	2868	<1	0.30	129	400	38	<5	<20	183	0.16	<10	81	<10	4	125
68	S07-33660	0.8	4.63	50	695	<5	1.96	<1	15	163	88	2.87	1.73	20	1.94	3248	<1	0.42	139	450	34	<5	<20	215	0.15	<10	75	<10	5	179
69	S07-33661	0.8	4.60	30	740	<5	1.84	<1	15	153	61	2.92	1.58	20	1.83	2794	<1	0.25	104	360	40	<5	<20	196	0.16	<10	78	<10	4	84
70	S07-33662	0.6	3.46	15	525	<5	1.33	<1	6	199	32	1.47	1.38	20	0.76	974	<1	0.69	23	430	28	<5	<20	154	0.13	<10	35	<10	4	38
71	S07-33663	0.4	3.53	10	455	<5	1.82	<1	6	245	21	1.44	1.21	20	0.72	829	<1	0.76	17	470	30	<5	<20	168	0.13	<10	32	<10	4	33
72	S07-33664	6.4	3.91	150	135	<5	0.38	<1	7	39	49	3.56	2.97	<10	0.26	247	6	0.47	22	450	32	65	<20	106	0.28	<10	50	<10	9	50
73	S07-33665	<0.2	2.92	10	355	<5	1.68	<1	4	206	23	1.39	0.98	20	0.67	523	<1	0.61	15	420	20	<5	<20	158	0.13	<10	26	<10	4	26
74	S07-33666	0.2	4.47	30	665	<5	2.27	<1	12	207	41	1.87	1.58	20	1.06	687	<1	0.58	49	470	26	<5	<20	229	0.15	<10	63	<10	5	55
75	S07-33667	0.4	3.67	5	465	<5	2.65	<1	4	199	23	1.69	1.29	20	0.94	684	<1	0.68	17	1610	24	<5	<20	276	0.14	<10	36	<10	7	31
76	S07-33668	0.4	5.31	30	255	<5	2.55	1	14	240	76	2.89	1.74	30	1.27	670	9	0.71	41	640	36	<5	<20	239	0.15	<10	63	<10	5	183
77	S07-33669	0.2	4.89	20	730	<5	2.10	<1	9	183	49	2.03	1.63	20	1.17	565	6	0.65	32	600	30	<5	<20	220	0.16	<10	65	<10	5	54
78	S07-33670	0.6	5.17	15	715	<5	2.14	<1	7	217	32	1.93	1.81	20	1.05	558	4	0.79	22	570	28	<5	<20	214	0.17	<10	55	<10	5	40
79	S07-33671	0.4	4.27	10	605	<5	2.09	<1	7	200	34	1.73	1.61	20	0.98	537	3	0.72	21	490	26	<5	<20	218	0.15	<10	48	<10	5	42
80	S07-33672	0.2	4.77	20	685	<5	1.93	<1	13	266	45	1.72	1.76	20	0.94	357	3	0.80	55	810	30	<5	<20	211	0.17	<10	67	<10	6	47
81	S07-33673	0.4	6.48	20	710	<5	3.57	<1	11	197	58	2.44	1.88	30	1.53	608	1	0.73	41	690	44	<5	<20	319	0.23	<10	98	<10	8	56
82	S07-33674	<0.2	0.09	<5	20	<5	>10	<1	<1	3	8	0.51	0.03	<10	>10	212	<1	0.02	2	210	6	<5	<20	49	<0.01	<10	4	<10	<1	12
83	S07-33675	0.4	2.82	10	355	<5	1.97	<1	5	223	24	1.89	1.01	20	0.91	531	<1	0.47	17	450	20	<5	<20	216	0.13	<10	32	<10	5	40
84	S07-33676	0.4	3.85	15	535	<5	2.58	<1	6	284	21	1.96	1.48	20	0.97	518	1	0.47	25	450	94	<5	<20	221	0.14	<10	44	<10	5	38
85	S07-33677	0.4	3.54	20	545	<5	2.04	<1	6	213	15	1.42	1.46	20	0.82	547	<1	0.43	25	440	16	<5	<20	189	0.14	<10	41	<10	4	34
86	S07-33678	0.6	3.64	20	500	<5	2.50	<1	6	199	15	1.76	1.12	20	0.99	882	<1	0.13	23	430	22	<5	<20	219	0.15	<10	39	<10	5	50
87	S07-33679	0.4	3.71	35	470	<5	2.53	<1	8	360	54	1.97	1.22	20	1.13	979	<1	0.23	48	420	22	5	<20	244	0.15	<10	45	<10	6	50
88	S07-33680	0.2	3.73	15	460	<5	1.77	<1	6	202	29	1.50	1.28	20	0.78	530	<1	0.55	18	430	20	<5	<20	171	0.14	<10	34	<10	5	39

IC DATA:

Repeat:

1	S07-33593	0.8	6.65	55	230	<5	4.01	<1	20	267	130	5.69	1.84	10	1.42	1102	1	2.41	15	1600	34	<5	<20	563	0.21	<10	179	<10	7	40
10	S07-33602	1.1	7.53	35	780	<5	3.13	<1	13	110	52	4.63	2.34	10	1.49	1126	1	1.76	17	1260	356	<5	<20	338	0.19	<10	122	<10	7	91
19	S07-33611	0.4	6.76	10	555	<5	2.19	<1	10	105	48	3.02	1.90	10	0.98	712	<1	2.22	11	620	32	<5	<20	300	0.15	<10	79	<10	6	46
36	S07-33628	0.4	7.40	15	900	<5	4.04	<1	24	110	83	5.55	1.58	<10	3.04	1250	<1	2.68	36	1060	30	<5	<20	410	0.22	<10	219	<10	7	61
45	S07-33637	1.0	3.86	30	250	<5	1.71	1	14	266	79	2.95	1.77	20	1.13	752	6	0.08	115	510	26	<5	<20	128	0.10	<10	76	<10	4	198
54	S07-33646	0.6	5.74	40	280	<5	2.33	<1	23	216	73	3.40	2.08	20	1.61	2186	2	0.25	121	490	36	<5	<20	229	0.16	<10	115	<10	6	171
71	S07-33663	0.4	3.49	10	460	<5	1.68	<1	5	246	22	1.40	1.24	20	0.72	801	<1	0.79	17	460	30	<5	<20	167	0.13	<10	33	<10	4	32
80	S07-33672	0.4	4.88	25	680	<5	2.00	<1	12	282	46	1.69	1.39	20	0.94	356	3	0.79	53	790	28	<5	<20	212	0.17	<10	66	<10	6	44

Resplit:

1	S07-33593	0.8	7.05	55	275	<5	4.20	<1	16	273	140	5.28	1.83	10	1.53	1102	<1	2.18	13	1600	36	<5	<20	545	0.20	<10	174	<10	8	39
36	S07-33628	0.4	7.57	25	970	<5	3.85	<1	25	97	81	5.66	1.62	10	3.10	1284	<1	2.61	39	1140	32	<5	<20	414	0.28	<10	228	<10	7	63
71	S07-33663	0.4	3.51	10	470	<5	1.81	<1	5	232	21	1.31	1.21	20	0.72	796	<1	0.77	15	470	26	<5	<20	170	0.13	<10	32	<10	4	31

Standard:

std3		0.4	5.66	20	1245	<5	2.22	<1	15	57	35	4.05	1.54	30	1.38	2626	5	1.33	33	1730	64	<5	<20	259	0.32	<10	102	<10	28	201
std3		0.5	5.41	20	1250	<5	2.32	<1	14	58	34	3.77	1.39	30	1.38	2617	5	1.29	31	1700	64	<5	<20	266	0.30	<10	104	<10	28	195
std3		0.5	5.63	20	1245	<5	2.16	<1	15	58	34	3.95	1.10	30	1.38	2712	5	1.29	32	1760	66	<5	<20	263	0.31	<10	104	<10	27	196


CP: 4 ACID DIGEST/ICP-FINISH


AG: 4 ACID DIGEST/AA-FINISH

J/nw

1/td2270s

11/1/07


ECO TECH LABORATORY LTD.
 Jutta Sealouse
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2232

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

25-Feb-08

Attention: Bob Singh

No. of samples received: 97

Sample Type: Core

Project: Spanish Mountain


Shipment #: SMC-07-133

Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-33495	0.43	0.013
2	S07-33496	0.11	0.003
3	S07-33497	0.25	0.007
4	S07-33498	0.07	0.002
5	S07-33499	0.09	0.003
6	S07-33500	0.14	0.004
7	S07-33501	0.20	0.006
8	S07-33502	0.20	0.006
9	S07-33503	* <0.03	<0.001
10	S07-33504	0.17	0.005
11	S07-33505	0.15	0.004
12	S07-33506	0.10	0.003
13	S07-33507	0.17	0.005
14	S07-33508	0.18	0.005
15	S07-33509	0.23	0.007
16	S07-33511	0.27	0.008
17	S07-33512	0.25	0.007
18	S07-33513	0.13	0.004
19	S07-33514	0.12	0.004
20	S07-33515	0.11	0.003
21	S07-33516	0.28	0.008
22	S07-33517	0.48	0.014
23	S07-33518	0.08	0.002
24	S07-33519	0.07	0.002
25	S07-33520	0.25	0.007
26	S07-33521	<0.03	<0.001
27	S07-33522	<0.03	<0.001
28	S07-33523	<0.03	<0.001
29	S07-33524	<0.03	<0.001
30	S07-33525	<0.03	<0.001

* = 30g FA


ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
31	S07-33526	<0.03	<0.001
32	S07-33527	<0.03	<0.001
33	S07-33528	<0.03	<0.001
34	S07-33529	<0.03	<0.001
35	S07-33530	<0.03	<0.001
36	S07-33531	0.06	0.002
37	S07-33532	<0.03	<0.001
38	S07-33533	0.06	0.002
39	S07-33534	* <0.03	<0.001
40	S07-33535	0.04	0.001
41	S07-33536	0.04	0.001
42	S07-33537	0.06	0.002
43	S07-33538	0.76	0.022
44	S07-33539	0.05	0.001
45	S07-33540	* 0.41	0.012
46	S07-33541	<0.03	<0.001
47	S07-33542	0.04	0.001
48	S07-33543	0.11	0.003
49	S07-33544	0.34	0.010
50	S07-33545	0.33	0.010
51	S07-33546	0.95	0.028
52	S07-33547	0.03	0.001
53	S07-33548	<0.03	<0.001
54	S07-33549	0.13	0.004
55	S07-33550	<0.03	<0.001
56	S07-33551	<0.03	<0.001
57	S07-33552	0.06	0.002
58	S07-33553	0.28	0.008
59	S07-33554	18.33	0.534
60	S07-33555	0.47	0.014
61	S07-33556	1.64	0.048
62	S07-33557	0.30	0.009
63	S07-33558	0.36	0.011
64	S07-33559	0.17	0.005
65	S07-33560	0.43	0.012
66	S07-33561	0.27	0.008
67	S07-33562	2.09	0.061
68	S07-33563	0.05	0.001
69	S07-33564	* <0.03	<0.001
70	S07-33565	1.17	0.034
71	S07-33566	0.04	0.001
72	S07-33567	<0.03	<0.001
73	S07-33568	0.48	0.014

* = 30g FA



 ECO TECH LABORATORY LTD.

Jutta Jealous

B.C. Certified Assayer

Metallc Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
74	S07-33569	0.53	0.015
75	S07-33570	0.25	0.007
76	S07-33571	0.14	0.004
77	S07-33572	6.71	0.196
78	S07-33573	<0.03	<0.001
79	S07-33574	0.10	0.003
80	S07-33575	<0.03	<0.001
81	S07-33576	<0.03	<0.001
82	S07-33577	0.09	0.003
83	S07-33578	<0.03	<0.001
84	S07-33579	<0.03	<0.001
85	S07-33580	0.18	0.005
86	S07-33581	<0.03	<0.001
87	S07-33582	<0.03	<0.001
88	S07-33583	0.03	0.001
89	S07-33584	<0.03	<0.001
90	S07-33585	<0.03	<0.001
91	S07-33586	0.14	0.004
92	S07-33587	3.82	0.111
93	S07-33588	0.51	0.015
94	S07-33589	2.04	0.059
95	S07-33590	0.15	0.004
96	S07-33591	0.05	0.002
97	S07-33592	1.46	0.043

QC DATA:

Resplit:

1	S07-33495	0.32	0.009
36	S07-33531	0.04	0.001
71	S07-33566	0.06	0.002


Standard:

OxI54	1.88	0.055
OxI54	1.82	0.053
OxI54	1.84	0.054
OxI54	1.84	0.054
OxI54	1.89	0.055
OxI54	1.85	0.054
OxI54	1.81	0.053

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw
XLS/07



ECO TECH LABORATORY LTD.

Jutta Jgalouse
B.C. Certified Assayer

ECO TECH LABORATORY LTD.

10041 Dallas Drive

KAMLOOPS, B.C.

V2C 6T4

Phone: 250-573-5700

Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS 2007-2232

Skygold Ventures

615 - 800 W. Pender Street

Vancouver, BC

V6B 2V6

No. of samples received: 97

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-133

Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-33495	1.2	4.92	35	265	<5	2.07	3	16	301	89	5.30	2.12	20	0.96	565	30	0.21	81	970	48	10	<20	109	0.12	<10	307	<10	7	166
2	S07-33496	1.4	4.78	20	245	<5	2.95	2	14	204	90	4.90	2.19	20	1.41	685	31	0.12	78	830	54	5	<20	128	0.10	<10	268	<10	6	124
3	S07-33497	1.0	5.07	75	305	<5	3.03	1	28	563	79	5.39	2.11	20	2.46	852	28	0.20	228	950	46	10	<20	144	0.10	<10	260	<10	7	139
4	S07-33498	1.2	5.15	70	400	<5	4.32	1	32	618	59	5.38	2.10	10	5.12	1551	8	0.30	208	600	34	15	<20	212	0.07	<10	136	<10	7	134
5	S07-33499	1.0	4.78	45	365	<5	6.19	1	10	426	43	3.78	2.09	20	3.02	1542	12	0.14	103	610	34	10	<20	263	0.06	<10	87	<10	10	107
6	S07-33500	1.4	4.70	15	270	<5	3.36	2	12	189	49	3.94	2.14	20	1.76	828	17	0.11	53	720	46	5	<20	139	0.05	<10	146	<10	8	120
7	S07-33501	1.6	5.46	25	190	<5	4.14	3	19	183	74	5.92	2.24	20	1.87	1085	27	0.12	88	1190	60	10	<20	169	0.07	<10	237	<10	8	227
8	S07-33502	1.6	5.13	20	250	<5	3.81	3	18	332	71	5.26	2.15	20	1.78	1036	28	0.12	90	1060	56	10	<20	148	0.06	<10	239	<10	7	202
9	S07-33503	0.2	7.49	5	510	<5	3.14	<1	11	83	34	4.55	0.78	10	1.35	856	3	2.71	28	860	28	<5	<20	377	0.38	<10	103	<10	17	54
10	S07-33504	2.0	5.16	20	200	<5	2.93	3	19	445	71	5.41	2.31	20	1.61	904	32	0.13	92	1080	58	15	<20	137	0.07	<10	261	<10	8	256
11	S07-33505	1.8	4.85	25	195	<5	3.92	2	19	470	74	5.09	2.21	20	1.83	964	25	0.12	94	2130	46	15	<20	167	0.07	<10	246	<10	11	190
12	S07-33506	1.0	4.64	15	240	<5	4.38	2	17	278	85	4.14	1.98	20	2.13	1190	13	0.26	71	860	34	5	<20	183	0.09	<10	217	<10	8	204
13	S07-33507	1.6	5.04	25	210	<5	3.51	2	19	423	78	5.50	2.24	20	1.72	944	29	0.12	94	970	48	10	<20	138	0.09	<10	252	<10	7	232
14	S07-33508	1.6	4.71	25	225	<5	3.47	2	18	453	68	5.25	2.12	20	1.73	992	25	0.12	89	1010	46	15	<20	141	0.09	<10	244	<10	8	230
15	S07-33509	2.4	5.62	20	225	<5	3.08	3	19	393	65	5.89	2.22	20	1.37	916	35	0.12	82	1160	74	15	<20	113	0.10	<10	259	<10	7	255
16	S07-33511	2.6	5.47	25	225	<5	3.13	3	17	442	62	5.53	2.11	20	1.43	940	34	0.53	78	1090	82	15	<20	145	0.10	<10	263	<10	7	275
17	S07-33512	2.6	5.13	20	160	<5	3.15	3	17	407	67	5.47	2.29	20	1.50	962	35	0.12	78	1130	82	15	<20	126	0.09	<10	264	<10	7	260
18	S07-33513	2.2	4.97	20	120	<5	2.49	3	17	425	55	5.15	2.19	20	1.20	769	28	0.11	73	1240	62	15	<20	106	0.09	<10	247	<10	7	260
19	S07-33514	1.0	5.66	15	225	<5	3.33	3	21	464	43	5.70	2.31	20	1.23	895	30	0.11	77	3280	42	10	<20	126	0.11	<10	243	<10	8	261
20	S07-33515	0.4	5.24	25	220	<5	3.32	2	16	351	62	4.93	1.92	10	1.39	843	21	0.17	58	1460	30	5	<20	124	0.10	<10	161	<10	6	192
21	S07-33516	0.6	6.64	25	395	<5	3.99	<1	13	206	128	3.69	2.29	10	1.83	900	5	0.56	25	920	32	5	<20	173	0.10	<10	126	<10	8	136
22	S07-33517	0.6	5.83	30	335	<5	1.81	<1	15	331	64	4.88	1.98	20	1.42	547	9	0.88	34	590	26	5	<20	123	0.10	<10	143	<10	7	169
23	S07-33518	0.4	5.59	15	325	<5	2.82	<1	12	425	43	4.06	1.83	20	1.58	780	7	0.91	27	610	22	10	<20	166	0.10	<10	129	<10	7	121
24	S07-33519	0.6	6.61	25	505	<5	2.20	2	14	400	72	4.51	2.16	20	1.69	669	13	1.24	47	740	30	10	<20	152	0.13	<10	252	<10	7	201
25	S07-33520	0.4	6.06	20	355	<5	2.83	2	11	271	61	3.77	1.88	20	1.63	770	13	1.33	36	700	28	5	<20	176	0.10	<10	206	<10	6	163

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
26	S07-33521	0.4	7.35	15	400	<5	2.94	<1	15	460	66	5.03	2.42	20	1.95	829	3	1.47	24	1030	32	10	<20	198	0.10	<10	136	<10	8	135
27	S07-33522	0.4	7.62	10	1185	<5	2.09	<1	11	340	54	4.19	2.29	10	1.99	733	3	1.93	22	780	32	5	<20	188	0.11	<10	145	<10	6	94
28	S07-33523	0.2	7.93	5	1345	<5	1.99	<1	10	311	56	4.14	2.33	10	2.09	747	2	1.99	22	800	36	5	<20	188	0.12	<10	148	<10	6	112
29	S07-33524	0.2	7.26	10	905	<5	1.79	<1	11	241	63	4.22	1.84	20	1.76	617	10	2.20	30	790	32	<5	<20	158	0.11	<10	174	<10	5	128
30	S07-33525	0.2	6.87	5	1360	<5	1.41	<1	11	61	59	3.80	1.93	20	1.91	561	3	2.30	18	720	30	<5	<20	151	0.11	<10	129	<10	5	88
31	S07-33526	0.6	6.45	10	1315	<5	1.53	<1	12	70	57	3.75	2.02	10	1.99	594	2	2.11	18	620	28	<5	<20	153	0.10	<10	128	<10	5	92
32	S07-33527	0.6	6.43	15	255	<5	1.88	<1	19	88	61	4.10	1.91	20	1.54	544	4	1.61	21	610	32	<5	<20	143	0.09	<10	110	<10	6	107
33	S07-33528	0.6	6.81	5	1685	<5	2.19	<1	7	62	37	2.49	2.25	20	1.51	599	7	1.73	14	620	30	<5	<20	167	0.12	<10	98	<10	8	64
34	S07-33529	0.2	6.08	10	1135	<5	1.51	<1	8	93	38	2.72	1.66	20	1.34	469	4	1.66	22	590	24	<5	<20	123	0.13	<10	122	<10	6	117
35	S07-33530	0.4	6.83	10	1030	<5	1.65	1	14	115	124	4.07	2.17	20	1.73	512	19	1.75	49	850	38	<5	<20	139	0.12	<10	257	<10	6	212
36	S07-33531	0.6	6.94	10	335	<5	2.01	<1	23	100	90	5.36	2.17	20	1.72	601	12	1.54	47	960	50	<5	<20	137	0.11	<10	203	<10	6	173
37	S07-33532	0.4	7.29	5	645	<5	2.94	<1	18	107	90	4.93	1.88	20	1.64	629	<1	1.99	39	1140	34	<5	<20	159	0.13	<10	140	<10	5	121
38	S07-33533	0.8	5.63	5	260	<5	2.64	<1	12	120	84	4.03	1.76	20	1.13	530	28	1.26	43	720	28	<5	<20	120	0.10	<10	141	<10	5	114
39	S07-33534	<0.2	4.74	15	145	<5	3.81	1	18	455	72	4.40	1.77	10	1.10	791	6	0.98	39	830	24	5	<20	195	0.11	<10	191	<10	6	151
40	S07-33535	0.4	6.99	15	495	<5	5.51	1	17	106	68	5.22	2.22	10	2.33	917	13	1.05	33	1140	36	<5	<20	211	0.11	<10	203	<10	7	169
41	S07-33536	0.8	7.41	10	775	<5	4.64	<1	16	92	101	4.71	2.21	10	1.94	784	13	1.48	29	880	34	<5	<20	204	0.13	<10	264	<10	6	151
42	S07-33537	0.6	7.98	10	430	<5	6.76	<1	13	94	90	5.31	2.44	20	2.47	1075	12	1.03	26	1120	44	<5	<20	249	0.13	<10	178	<10	9	157
43	S07-33538	1.4	6.16	10	360	<5	5.65	1	12	146	45	4.38	2.04	20	2.01	1058	11	0.86	33	1210	26	<5	<20	257	0.11	<10	245	<10	7	153
44	S07-33539	0.4	4.51	10	225	<5	4.30	1	17	457	74	4.12	1.77	10	1.15	734	5	0.96	34	730	22	5	<20	205	0.11	<10	190	<10	6	132
45	S07-33540	0.9	5.47	95	360	<5	0.27	<1	8	25	30	3.34	4.15	10	0.33	186	3	0.11	15	500	20	45	<20	55	0.41	<10	66	<10	12	47
46	S07-33541	0.4	6.66	<5	590	<5	>10	<1	16	193	82	4.35	2.16	20	1.82	1747	5	1.79	24	1100	30	<5	<20	395	0.14	<10	179	<10	9	101
47	S07-33542	0.4	7.54	10	650	<5	5.66	1	20	348	71	5.22	2.22	10	2.16	1170	22	1.39	30	1100	40	5	<20	250	0.18	<10	342	<10	8	189
48	S07-33543	0.4	6.56	10	355	<5	4.12	<1	20	259	104	5.19	2.15	10	1.79	898	10	1.19	34	670	34	<5	<20	198	0.14	<10	231	<10	6	161
49	S07-33544	0.6	7.72	15	290	<5	4.61	1	16	290	77	6.20	2.19	20	2.12	986	16	1.09	29	1280	48	<5	<20	206	0.17	<10	213	<10	9	209
50	S07-33545	0.8	7.40	10	275	<5	5.15	1	21	114	106	5.50	2.06	20	1.92	968	12	0.93	38	920	42	<5	<20	206	0.14	<10	238	<10	7	174
51	S07-33546	1.2	7.63	15	150	<5	4.76	1	28	96	83	7.12	2.37	10	1.50	917	8	1.00	43	870	36	<5	<20	173	0.12	<10	177	<10	6	142
52	S07-33547	0.4	6.16	10	680	<5	3.89	<1	11	112	47	3.20	2.05	20	1.40	751	2	1.50	30	780	24	<5	<20	186	0.13	<10	104	<10	7	99
53	S07-33548	0.2	6.98	10	700	<5	5.25	<1	11	80	36	4.00	2.17	20	2.05	1144	1	1.87	12	780	28	<5	<20	249	0.11	<10	97	<10	8	57
54	S07-33549	0.2	7.54	5	1025	<5	4.60	<1	8	57	37	2.95	2.39	20	1.62	842	<1	1.62	10	610	30	<5	<20	209	0.12	<10	71	<10	11	43
55	S07-33550	0.2	6.65	<5	935	<5	4.40	<1	8	166	43	2.83	2.19	20	1.66	931	2	1.42	14	560	28	<5	<20	202	0.14	<10	84	<10	9	65
56	S07-33551	0.6	7.20	<5	950	<5	4.93	<1	11	227	50	3.30	2.18	20	1.75	1109	3	1.47	18	620	34	<5	<20	215	0.15	<10	89	<10	10	80
57	S07-33552	0.4	4.90	15	195	<5	2.32	<1	14	435	36	4.78	1.36	10	0.81	574	13	1.28	24	620	26	10	<20	128	0.11	<10	97	<10	8	44
58	S07-33553	0.6	7.08	10	525	<5	3.21	<1	11	197	64	4.07	2.09	20	1.49	837	1	1.36	12	760	32	<5	<20	184	0.19	<10	102	<10	10	69
59	S07-33554	12.2	8.56	15	285	<5	4.36	<1	15	373	72	5.77	2.20	20	1.64	1105	<1	0.85	18	1340	192	5	<20	181	0.27	<10	125	<10	10	87
60	S07-33555	0.8	7.43	<5	390	<5	3.37	<1	21	3324	71	8.07	2.49	20	1.88	1208	2	0.58	50	1480	50	50	<20	184	0.21	<10	115	<10	10	140
61	S07-33556	1.0	7.60	15	270	<5	4.81	<1	26	173	80	7.24	2.21	20	2.05	1582	<1	0.61	27	1820	64	<5	<20	275	0.22	<10	135	<10	10	144
62	S07-33557	1.2	6.46	10	720	<5	3.24	<1	12	237	43	4.93	2.19	20	1.65	1224	<1	0.64	12	1230	42	<5	<20	202	0.21	<10	92	<10	7	93
63	S07-33558	1.0	8.91	15	735	<5	5.21	<1	21	154	84	6.20	2.16	10	1.98	1532	<1	1.38	24	1150	46	<5	<20	293	0.27	<10	174	<10	6	94
64	S07-33559	0.8	7.56	20	305	<5	4.01	<1	21	290	72	6.26	2.09	10	1.73	1082	<1	1.83	20	990	38	<5	<20	289	0.20	<10	175	<10	7	89
65	S07-33560	0.8	7.02	15	420	<5	4.17	<1	15	389	64	5.32	2.16	10	1.48	1161	3	1.49	25	920	42	5	<20	273	0.21	<10	144	<10	7	75

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
66	S07-33561	0.8	7.36	35	520	<5	3.16	<1	20	95	74	5.49	2.34	10	1.76	987	1	2.13	24	790	40	<5	<20	282	0.18	<10	181	<10	8	86
67	S07-33562	0.6	8.05	20	800	<5	4.84	<1	15	148	67	4.48	2.58	20	1.72	1311	1	1.20	28	920	68	<5	<20	416	0.24	<10	171	<10	10	46
68	S07-33563	0.4	7.62	15	605	<5	3.74	<1	18	78	38	5.49	2.27	10	1.87	1202	<1	2.22	23	740	34	<5	<20	317	0.21	<10	154	<10	5	97
69	S07-33564	0.2	0.06	<5	25	<5	>10	<1	<1	1	3	0.53	0.02	<10	>10	198	<1	0.02	2	160	<2	<5	<20	43	<0.01	<10	2	<10	<1	12
70	S07-33565	1.2	5.79	25	120	<5	2.30	<1	20	228	73	5.35	1.96	10	1.14	833	2	1.57	34	570	30	<5	<20	207	0.15	<10	149	<10	5	45
71	S07-33566	0.4	8.60	10	815	<5	3.85	<1	26	114	71	6.16	2.50	10	1.93	1340	<1	2.54	24	1040	40	<5	<20	316	0.24	<10	211	<10	6	101
72	S07-33567	0.6	8.74	15	895	<5	4.37	<1	24	107	69	6.24	2.83	10	2.22	1646	<1	1.86	21	1230	40	<5	<20	360	0.26	<10	220	<10	6	105
73	S07-33568	0.8	7.16	25	360	<5	3.51	<1	12	112	70	4.52	2.52	20	1.24	973	17	1.58	14	850	32	<5	<20	257	0.19	<10	126	<10	7	55
74	S07-33569	0.6	8.45	20	770	<5	4.92	<1	22	109	61	5.47	2.77	10	2.11	1566	1	1.08	32	940	38	<5	<20	327	0.21	<10	204	<10	6	61
75	S07-33570	0.6	8.74	15	680	<5	5.35	<1	21	52	71	5.15	2.65	10	2.14	1570	<1	2.21	25	1130	36	<5	<20	348	0.22	<10	185	<10	5	53
76	S07-33571	0.4	9.38	15	700	<5	5.74	<1	17	109	40	5.39	2.87	10	2.22	1581	<1	2.07	25	1300	36	<5	<20	405	0.25	<10	191	<10	6	51
77	S07-33572	6.3	3.95	150	300	<5	0.41	<1	7	40	50	3.56	2.95	<10	0.25	246	6	0.52	21	450	28	65	<20	95	0.31	<10	49	<10	10	47
78	S07-33573	0.4	8.49	10	445	<5	4.03	<1	15	74	56	4.57	2.15	10	1.65	1100	<1	2.93	14	1140	30	<5	<20	377	0.25	<10	149	<10	6	65
79	S07-33574	0.4	8.02	15	485	<5	6.27	<1	15	100	41	5.44	2.41	10	2.00	1495	<1	2.57	21	1200	30	<5	<20	362	0.22	<10	161	<10	10	52
80	S07-33575	0.6	8.88	15	650	<5	3.83	<1	19	81	67	6.19	2.80	10	2.20	1064	<1	1.03	24	970	32	<5	<20	256	0.24	<10	183	<10	5	68
81	S07-33576	0.4	8.51	15	760	<5	4.27	<1	20	78	51	5.56	2.93	10	2.23	1228	<1	1.83	21	960	32	<5	<20	319	0.24	<10	189	<10	6	61
82	S07-33577	0.8	9.00	25	880	<5	5.35	<1	20	92	76	5.55	3.01	10	2.16	1466	<1	1.16	22	1070	42	<5	<20	268	0.29	<10	190	<10	7	64
83	S07-33578	0.6	7.71	10	570	<5	3.80	<1	15	164	79	4.79	2.37	10	1.83	1060	<1	2.27	23	880	30	<5	<20	250	0.21	<10	160	<10	4	57
84	S07-33579	0.6	8.12	10	495	<5	3.44	<1	18	69	61	5.15	2.42	<10	2.07	994	<1	2.42	21	880	32	<5	<20	287	0.22	<10	189	<10	4	60
85	S07-33580	0.8	8.05	15	545	<5	3.39	<1	17	73	57	5.22	2.56	10	1.99	987	<1	2.35	21	940	30	<5	<20	244	0.21	<10	174	<10	4	55
86	S07-33581	0.8	8.73	10	585	<5	4.28	<1	20	71	73	5.62	2.27	10	2.17	1244	<1	2.86	20	950	32	<5	<20	369	0.20	<10	199	<10	5	50
87	S07-33582	0.4	8.19	5	695	<5	3.97	<1	18	55	70	5.17	2.60	<10	2.16	1169	<1	1.97	19	810	30	<5	<20	381	0.21	<10	221	<10	5	67
88	S07-33583	0.2	8.45	10	805	<5	4.51	<1	18	98	59	5.34	2.58	10	2.04	1200	<1	1.84	21	840	36	<5	<20	384	0.20	<10	217	<10	5	54
89	S07-33584	0.2	7.21	5	580	<5	3.57	<1	14	96	60	4.35	2.53	<10	1.55	985	<1	1.78	16	680	24	<5	<20	260	0.21	<10	170	<10	4	41
90	S07-33585	0.4	7.43	10	700	<5	4.02	<1	11	113	50	3.75	2.59	20	1.22	830	<1	1.35	13	750	26	<5	<20	275	0.20	<10	104	<10	6	48
91	S07-33586	0.8	7.16	10	630	<5	4.53	<1	11	144	72	3.92	2.54	20	1.34	886	<1	1.52	15	760	26	<5	<20	359	0.18	<10	115	<10	7	47
92	S07-33587	1.4	6.80	10	400	<5	4.62	<1	18	174	242	5.35	2.39	20	1.68	1130	<1	1.44	14	1650	36	<5	<20	338	0.27	<10	206	<10	12	68
93	S07-33588	0.8	7.46	10	420	<5	4.84	<1	19	100	228	6.73	2.23	20	1.78	1226	1	1.76	12	1830	68	<5	<20	320	0.29	<10	221	<10	12	74
94	S07-33589	4.7	4.64	105	320	<5	0.51	1	11	34	629	5.45	2.51	10	1.73	389	7	0.31	22	520	98	50	<20	71	0.28	<10	55	<10	11	666
95	S07-33590	1.0	7.40	15	615	<5	4.24	<1	18	93	223	6.18	2.56	20	1.70	1101	<1	1.09	10	1850	30	<5	<20	305	0.32	<10	233	<10	14	65
96	S07-33591	0.8	7.81	10	580	<5	5.05	<1	20	91	265	7.16	2.67	20	1.67	1265	<1	0.82	12	1970	34	<5	<20	283	0.33	<10	230	<10	12	93
97	S07-33592	0.6	7.63	10	510	<5	4.80	<1	17	109	216	6.47	2.51	10	1.53	1133	<1	2.14	11	1760	30	<5	<20	485	0.34	<10	215	<10	11	63

QC DATA:


Repeat:

1	S07-33495	1.2	5.02	25	255	<5	2.23	3	16	328	87	5.23	2.16	20	1.04	585	30	0.24	83	1010	52	10	<20	117	0.09	<10	307	<10	6	174
10	S07-33504	1.8	5.60	20	195	<5	3.28	3	20	440	74	5.87	2.35	20	1.65	969	34	0.12	99	1160	64	15	<20	139	0.08	<10	262	<10	8	272
19	S07-33514	1.2	5.51	15	215	<5	3.30	3	21	479	43	5.49	2.38	20	1.27	896	30	0.12	75	3280	42	10	<20	129	0.10	<10	249	<10	9	251
36	S07-33531	0.6	7.12	15	285	<5	2.11	<1	24	101	87	5.53	2.17	20	1.71	591	12	1.54	51	940	50	<5	<20	135	0.12	<10	205	<10	6	163
46	S07-33541	0.4	6.28	5	595	<5	>10	<1	15	207	83	4.34	2.07	20	1.81	1735	5	1.77	23	1090	28	<5	<20	391	0.13	<10	178	<10	9	99
54	S07-33549	0.3	7.22	<5	1010	<5	4.52	<1	11	57	34	2.78	2.23	10	1.60	834	<1	1.58	8	570	28	<5	<20	199	0.14	<10	74	<10	10	38
71	S07-33566	0.4	8.18	10	795	<5	3.99	<1	22	106	67	5.71	2.67	10	1.88	1291	<1	2.38	22	960	34	<5	<20	308	0.23	<10	208	<10	6	88
80	S07-33575	0.5	9.09	15	660	<5	3.82	<1	20	82	67	6.41	2.74	10	2.14	1073	<1	1.08	25	980	34	<5	<20	252	0.23	<10	190	<10	5	70
89	S07-33584	0.2	7.16	5	580	<5	3.66	<1	13	92	60	4.33	2.43	<10	1.54	981	<1	1.75	16	670	24	<5	<20	259	0.21	<10	170	<10	4	41


Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
Resplit:																														
1	S07-33495	1.4	4.76	25	200	<5	1.90	3	15	290	91	4.89	2.05	20	0.99	564	29	0.21	74	1000	54	5	<20	111	0.10	<10	290	<10	6	170
36	S07-33531	0.7	6.92	15	305	<5	1.90	1	17	98	94	5.12	2.07	20	1.61	551	14	1.52	46	880	46	<5	<20	133	0.14	<10	217	<10	5	180
71	S07-33566	0.4	8.53	15	795	<5	3.73	<1	23	107	75	5.79	2.48	10	1.75	1337	1	2.48	28	990	36	<5	<20	295	0.21	<10	209	<10	6	99
Standard:																														
STSD3		0.4	5.72	21	1250	<5	2.38	<1	17	59	38	4.16	1.40	30	1.31	2610	5	1.11	31	1710	63	<5	<20	288	0.36	<10	109	<10	29	191
STSD3		0.4	5.79	22	1230	<5	2.38	<1	15	60	35	4.18	1.56	30	1.37	2597	5	1.13	32	1600	58	<5	<20	275	0.35	<10	110	<10	28	203
STSD3		0.5	5.66	22	1285	<5	2.41	<1	15	61	34	4.13	1.51	40	1.36	2614	5	1.16	32	1680	60	<5	<20	277	0.35	<10	119	<10	30	204

ICP: 4 ACID DIGEST/ICP-FINISH
 AG: 4 ACID DIGEST/AA-FINISH

JJ/nl
 dt/d2232s
 XLS/07



ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2233

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

27-Feb-08

Attention: Bob Singh

No. of samples received: 228

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-134

Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-18651	<0.03	<0.001
2	S07-18652	<0.03	<0.001
3	S07-18653	0.09	0.003
4	S07-18654	0.40	0.012
5	S07-18655	2.03	0.059
6	S07-18656	<0.03	<0.001
7	S07-18657	0.03	0.001
8	S07-18658	0.03	0.001
9	S07-18659	<0.03	<0.001
10	S07-18660	<0.03	<0.001
11	S07-18661	0.03	0.001
12	S07-18662	<0.03	<0.001
13	S07-18663	<0.03	<0.001
14	S07-18664	<0.03	<0.001
15	S07-18665	<0.03	<0.001
16	S07-18666	<0.03	<0.001
17	S07-18667	<0.03	<0.001
18	S07-18668	<0.03	<0.001
19	S07-18669	<0.03	<0.001
20	S07-18670	<0.03	<0.001
21	S07-18671	<0.03	<0.001
22	S07-18672	<0.03	<0.001
23	S07-18673	<0.03	<0.001
24	S07-18674	<0.03	<0.001
25	S07-18675	<0.03	<0.001
26	S07-18676	<0.03	<0.001
27	S07-18677	<0.03	<0.001
28	S07-18678	<0.03	<0.001
29	S07-18679	<0.03	<0.001
30	S07-18680	<0.03	<0.001

* = 30g FA

[Signature]
ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
31	S07-18681	<0.03	<0.001
32	S07-18682	<0.03	<0.001
33	S07-18683	<0.03	<0.001
34	S07-18684	<0.03	<0.001
35	S07-18685	<0.03	<0.001
36	S07-18686	*	<0.03
37	S07-18687	<0.03	<0.001
38	S07-18688	<0.03	<0.001
39	S07-18689	<0.03	<0.001
40	S07-18690	0.14	0.004
41	S07-18691	0.04	0.001
42	S07-18692	0.09	0.003
43	S07-18693	0.12	0.004
44	S07-18694	<0.03	<0.001
45	S07-18695	<0.03	<0.001
46	S07-18696	<0.03	<0.001
47	S07-18697	<0.03	<0.001
48	S07-18698	<0.03	<0.001
49	S07-18699	<0.03	<0.001
50	S07-18700	*	0.44
51	S07-18701	0.03	0.001
52	S07-18702	<0.03	<0.001
53	S07-18703	0.12	0.003
54	S07-18704	<0.03	<0.001
55	S07-18705	<0.03	<0.001
56	S07-18706	0.07	0.002
57	S07-18707	0.09	0.003
58	S07-18708	0.16	0.005
59	S07-18709	<0.03	<0.001
60	S07-18710	*	<0.03
61	S07-18711	<0.03	<0.001
62	S07-18712	<0.03	<0.001
63	S07-18713	0.08	0.002
64	S07-18714	0.39	0.011
65	S07-18715	0.11	0.003
66	S07-18716	0.12	0.003
67	S07-18717	0.14	0.004
68	S07-18718	*	2.07
69	S07-18719	0.16	0.005
70	S07-18720	0.17	0.005
71	S07-18721	0.28	0.008
72	S07-18722	0.27	0.008
73	S07-18723	0.20	0.006

* = 30g FA

Jetta Jealouse
ECO TECH LABORATORY LTD.
 Jetta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
74	S07-18724	0.20	0.006
75	S07-18725	0.07	0.002
76	S07-18726	0.12	0.003
77	S07-18727	0.37	0.011
78	S07-18728	0.31	0.009
79	S07-18729	0.09	0.003
80	S07-18730	<0.03	<0.001
81	S07-18731	<0.03	<0.001
82	S07-18732	0.17	0.005
83	S07-18733	0.32	0.009
84	S07-18734	<0.03	<0.001
85	S07-18735	0.03	0.001
86	S07-18736	0.16	0.005
87	S07-18737	<0.03	<0.001
88	S07-18738	0.47	0.014
89	S07-18739	0.08	0.002
90	S07-18740	<0.03	<0.001
91	S07-18741	<0.03	<0.001
92	S07-18742	0.21	0.006
93	S07-18743	0.19	0.005
94	S07-18744	0.10	0.003
95	S07-18745	0.74	0.022
96	S07-18746	0.19	0.006
97	S07-18747	0.13	0.004
98	S07-18748	* 1.98	0.058
99	S07-18749	0.08	0.002
100	S07-18750	0.07	0.002
101	S07-18751	0.04	0.001
102	S07-18752	<0.03	<0.001
103	S07-18753	<0.03	<0.001
104	S07-18754	0.05	0.002
105	S07-18755	* <0.03	<0.001
106	S07-18756	<0.03	<0.001
107	S07-18757	<0.03	<0.001
108	S07-18758	0.26	0.008
109	S07-18759	<0.03	<0.001
110	S07-18760	0.10	0.003
111	S07-18761	<0.03	<0.001
112	S07-18762	<0.03	<0.001
113	S07-18763	<0.03	<0.001
114	S07-18764	<0.03	<0.001
115	S07-18765	0.04	0.001
116	S07-18766	<0.03	<0.001


* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
117	S07-18767	0.06	0.002
118	S07-18768	0.54	0.016
119	S07-18769	0.98	0.029
120	S07-18770	0.06	0.002
121	S07-18771	0.04	0.001
122	S07-18772	<0.03	<0.001
123	S07-18773	<0.03	<0.001
124	S07-18774	<0.03	<0.001
125	S07-18775	<0.03	<0.001
126	S07-18776	0.17	0.005
127	S07-18777	0.11	0.003
128	S07-18778	1.03	0.030
129	S07-18779	<0.03	<0.001
130	S07-18780	* <0.03	<0.001
131	S07-18781	0.04	0.001
132	S07-18782	<0.03	<0.001
133	S07-18783	<0.03	<0.001
134	S07-18784	<0.03	<0.001
135	S07-18785	<0.03	<0.001
136	S07-18786	0.12	0.004
137	S07-18787	0.04	0.001
138	S07-18788	<0.03	<0.001
139	S07-18789	<0.03	<0.001
140	S07-18790	0.06	0.002
141	S07-18791	0.07	0.002
142	S07-18792	0.04	0.001
143	S07-18793	0.12	0.003
144	S07-18794	* 0.45	0.013
145	S07-18795	<0.03	<0.001
146	S07-18796	0.05	0.001
147	S07-18797	<0.03	<0.001
148	S07-18798	0.07	0.002
149	S07-18799	<0.03	<0.001
150	S07-18800	0.04	0.001
151	S07-18801	0.18	0.005
152	S07-18802	0.10	0.003
153	S07-18803	0.15	0.004
154	S07-18804	0.15	0.004
155	S07-18805	1.04	0.030
156	S07-18806	0.43	0.013
157	S07-18807	1.19	0.035
158	S07-18808	0.04	0.001
159	S07-18809	1.38	0.040


* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
160	S07-18810	0.58	0.017
161	S07-18811	0.16	0.005
162	S07-18812	0.16	0.005
163	S07-18813	0.42	0.012
164	S07-18814	0.10	0.003
165	S07-18815	0.61	0.018
166	S07-18816	0.14	0.004
167	S07-18817	0.06	0.002
168	S07-18818	0.07	0.002
169	S07-18819	0.58	0.017
170	S07-18820	* <0.03	<0.001
171	S07-18821	0.08	0.002
172	S07-18822	0.11	0.003
173	S07-18823	0.21	0.006
174	S07-18824	0.36	0.011
175	S07-18825	0.36	0.011
176	S07-18826	<0.03	<0.001
177	S07-18827	<0.03	<0.001
178	S07-18828	* 2.06	0.060
179	S07-18829	<0.03	<0.001
180	S07-18830	<0.03	<0.001
181	S07-18831	<0.03	<0.001
182	S07-18832	0.04	0.001
183	S07-18833	0.05	0.001
184	S07-18834	0.08	0.002
185	S07-18835	0.07	0.002
186	S07-18836	0.06	0.002
187	S07-18837	0.17	0.005
188	S07-18838	0.09	0.002
189	S07-18839	0.05	0.001
190	S07-18840	0.17	0.005
191	S07-18841	<0.03	<0.001
192	S07-18842	<0.03	<0.001
193	S07-18843	<0.03	<0.001
194	S07-18844	<0.03	<0.001
195	S07-18845	0.17	0.005
196	S07-18846	0.05	0.001
197	S07-18847	0.05	0.001
198	S07-18848	1.41	0.041
199	S07-18849	0.08	0.002
200	S07-18850	<0.03	<0.001
201	S07-18851	0.12	0.003
202	S07-18852	* <0.03	<0.001

* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
203	S07-18853	0.08	0.002
204	S07-18854	0.04	0.001
205	S07-18855	0.03	0.001
206	S07-18856	0.06	0.002
207	S07-18857	0.43	0.013
208	S07-18858	0.10	0.003
209	S07-18859	<0.03	<0.001
210	S07-18860	0.69	0.020
211	S07-18861	0.21	0.006
212	S07-18862	2.10	0.061
213	S07-18863	0.41	0.012
214	S07-18864	1.27	0.037
215	S07-18865	1.52	0.044
216	S07-18866	0.50	0.014
217	S07-18867	0.16	0.005
218	S07-18868	0.13	0.004
219	S07-18869	0.14	0.004
220	S07-18870	0.53	0.015
221	S07-18871	0.15	0.004
222	S07-18872	0.29	0.008
223	S07-18873	0.30	0.009
224	S07-18874	0.05	0.002
225	S07-18875	0.77	0.022
226	S07-18876	0.72	0.021
227	S07-18877	0.63	0.018
228	S07-18878	0.08	0.002

QC DATA:**Resplit:**

1	S07-18651	<0.03	<0.001
37	S07-18687	<0.03	<0.001
71	S07-18721	0.24	0.007
106	S07-18756	<0.03	<0.001
141	S07-18791	0.07	0.002
176	S07-18826	0.03	0.001
211	S07-18861	0.18	0.005

Standard:

OXI54	1.87	0.055
OXI54	1.85	0.054
OXI54	1.87	0.055
OXI54	1.85	0.054
OXI54	1.81	0.053

* = 30g FA

Jutta Jealouse
ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays


ET #.	Tag #	Au (g/t)	Au (oz/t)
OXI54		1.83	0.053
OXI54		1.89	0.055
OXI54		1.89	0.055
OXI54		1.81	0.053
OXI54		1.84	0.054
OXI54		1.90	0.055
OXI54		1.85	0.054
OXI54		1.80	0.052
OXI54		1.82	0.053
OXI54		1.86	0.054
OXI54		1.82	0.053
OXI54		1.82	0.053
OXI54		1.88	0.055

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw

XLS/07


ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 2007-2233

Skygold Ventures
615 - 800 W. Pender Street
Vancouver, BC
V6B 2V6

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 228
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-134
Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-18651	0.2	5.67	60	290	<5	3.74	<1	28	414	75	5.47	1.20	10	3.67	1755	<1	1.25	135	930	34	10	<20	241	0.11	<10	166	<10	6	108
2	S07-18652	0.4	4.50	40	310	<5	3.51	<1	18	166	94	3.19	0.98	20	1.65	2054	2	1.07	93	500	32	<5	<20	200	0.10	<10	69	<10	7	80
3	S07-18653	0.4	4.63	10	335	<5	3.20	<1	22	177	80	3.53	1.09	20	1.20	2313	3	0.97	51	460	32	<5	<20	184	0.12	<10	72	<10	9	86
4	S07-18654	0.4	6.00	10	555	<5	3.64	<1	22	151	60	3.24	1.62	20	1.43	2600	2	1.05	42	460	48	<5	<20	233	0.13	<10	64	<10	8	75
5	S07-18655	4.4	4.20	190	270	<5	0.47	2	10	38	573	4.98	2.20	10	1.78	367	6	0.26	22	520	102	45	<20	76	0.26	<10	51	<10	10	681
6	S07-18656	<0.2	5.57	<5	655	<5	1.87	<1	6	84	25	2.22	1.79	10	1.36	1189	15	0.69	18	300	28	<5	<20	141	0.12	<10	20	<10	7	59
7	S07-18657	0.2	5.27	15	475	<5	3.65	<1	9	111	37	2.44	1.40	10	1.32	2754	28	0.94	31	390	26	<5	<20	199	0.12	<10	45	<10	9	67
8	S07-18658	<0.2	5.29	<5	475	<5	2.68	<1	10	89	65	2.75	1.42	20	1.15	1537	<1	1.19	31	390	28	<5	<20	176	0.13	<10	41	<10	9	55
9	S07-18659	0.2	4.16	25	255	<5	3.60	<1	18	227	71	3.78	0.88	20	2.13	1945	<1	0.97	87	510	30	<5	<20	217	0.10	<10	94	<10	6	69
10	S07-18660	<0.2	5.67	10	375	<5	2.93	<1	21	165	98	3.73	1.23	10	1.51	1453	<1	1.39	59	490	40	<5	<20	209	0.13	<10	112	<10	6	73
11	S07-18661	0.4	5.75	5	210	<5	2.49	<1	23	149	101	5.29	1.59	10	1.35	1407	<1	1.30	46	380	38	<5	<20	157	0.14	<10	109	<10	8	86
12	S07-18662	0.2	5.00	10	400	<5	0.96	<1	20	246	101	4.38	1.47	20	1.29	618	<1	1.00	46	590	36	<5	<20	105	0.12	<10	87	<10	6	85
13	S07-18663	0.2	5.60	15	645	<5	1.66	<1	13	140	61	2.52	1.85	20	1.11	897	6	0.87	33	350	30	<5	<20	136	0.11	<10	61	<10	7	56
14	S07-18664	0.2	5.40	15	490	<5	2.15	<1	11	144	63	2.73	1.67	20	1.19	994	1	1.17	27	380	28	<5	<20	166	0.10	<10	44	<10	8	48
15	S07-18665	0.4	4.67	30	260	<5	4.00	<1	30	530	81	4.84	1.11	<10	3.63	1072	5	0.99	161	710	30	10	<20	264	0.08	<10	132	<10	4	76
16	S07-18666	0.2	4.57	60	245	<5	7.15	<1	29	498	58	5.06	1.16	10	2.96	1344	21	0.81	192	630	32	10	<20	329	0.07	<10	130	<10	8	108
17	S07-18667	0.4	4.49	35	140	<5	4.79	1	29	508	67	5.70	1.11	20	2.58	841	46	0.63	219	630	30	10	<20	229	0.07	<10	190	<10	5	117
18	S07-18668	0.4	4.18	55	245	<5	3.62	<1	33	861	47	5.73	0.87	10	4.45	828	21	0.81	303	540	32	15	<20	214	0.06	<10	169	<10	5	110
19	S07-18669	0.2	4.79	70	125	<5	4.29	<1	50	901	65	6.47	0.68	<10	7.01	1080	6	1.14	446	770	30	20	<20	266	0.07	<10	160	<10	4	166
20	S07-18670	<0.2	4.11	120	130	<5	5.89	1	71	1039	55	6.70	0.71	<10	6.83	1121	<1	0.88	708	730	38	20	<20	297	0.04	<10	125	<10	3	210
21	S07-18671	0.2	3.77	185	110	<5	5.82	<1	66	1018	61	6.50	0.68	<10	6.60	1038	<1	0.84	668	680	38	20	<20	298	0.04	<10	119	<10	3	109
22	S07-18672	0.2	4.84	35	170	<5	4.22	<1	28	874	159	6.71	1.10	10	4.43	990	42	0.94	178	790	32	15	<20	249	0.10	<10	204	<10	7	107
23	S07-18673	0.2	3.52	30	60	<5	1.44	2	17	492	100	5.19	1.22	10	0.70	316	59	0.51	80	520	30	10	<20	77	0.11	<10	202	<10	5	140
24	S07-18674	0.2	3.93	25	185	<5	6.74	1	16	552	61	4.51	1.02	10	1.60	1160	24	0.63	85	590	28	10	<20	240	0.08	<10	124	<10	6	116
25	S07-18675	<0.2	4.78	35	320	<5	9.14	<1	20	339	44	4.45	1.16	10	3.43	1872	16	0.86	124	610	30	5	<20	401	0.07	<10	130	<10	8	89

Et #.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
26	S07-18676	0.2	3.80	60	195	<5	4.69	<1	39	917	51	5.62	0.75	<10	6.37	1249	4	0.77	363	610	24	15	<20	313	0.05	<10	116	<10	5	126
27	S07-18677	<0.2	4.06	30	270	<5	3.10	<1	20	314	51	3.69	0.99	10	2.22	726	4	0.75	76	530	28	5	<20	216	0.08	<10	104	<10	6	54
28	S07-18678	0.2	4.07	20	270	<5	2.97	<1	17	281	67	3.44	1.00	10	1.75	664	1	0.81	57	550	24	<5	<20	184	0.08	<10	100	<10	5	62
29	S07-18679	0.2	5.24	30	185	<5	5.12	1	22	302	77	4.92	1.30	10	1.76	1287	24	0.84	97	660	38	5	<20	216	0.10	<10	114	<10	7	121
30	S07-18680	0.4	6.93	30	210	<5	2.43	2	15	185	56	3.67	2.05	20	1.16	677	24	1.16	53	440	44	<5	<20	150	0.13	<10	101	<10	7	149
31	S07-18681	0.4	5.10	35	315	<5	9.30	1	28	534	70	5.39	1.32	<10	3.86	1769	6	0.81	160	860	32	10	<20	367	0.06	<10	152	<10	10	134
32	S07-18682	0.4	5.01	35	225	<5	4.53	1	21	372	51	4.15	1.38	20	1.89	1071	11	0.74	80	770	28	10	<20	229	0.09	<10	132	<10	7	126
33	S07-18683	0.2	6.53	25	225	<5	5.33	<1	25	385	58	4.75	1.48	10	2.39	1070	18	1.14	107	630	40	10	<20	289	0.11	<10	152	<10	8	45
34	S07-18684	0.4	5.03	40	180	<5	5.24	<1	33	617	41	5.92	1.00	<10	5.42	1257	4	1.13	193	820	24	10	<20	283	0.07	<10	169	<10	6	125
35	S07-18685	0.4	4.00	20	90	<5	3.38	2	20	507	100	6.82	1.21	20	1.36	723	64	0.51	112	830	26	10	<20	144	0.09	<10	218	<10	7	131
36	S07-18686	<0.2	7.18	<5	470	<5	2.62	<1	10	82	39	4.32	1.06	10	1.28	780	3	2.71	27	840	26	<5	<20	364	0.34	<10	101	<10	17	51
37	S07-18687	0.2	5.15	25	220	<5	4.57	<1	28	396	77	5.56	1.25	<10	3.35	1020	16	0.97	134	890	28	5	<20	244	0.10	<10	192	<10	8	88
38	S07-18688	0.4	6.08	20	310	<5	3.48	<1	28	377	75	5.90	1.34	<10	4.02	950	10	1.19	140	1110	34	10	<20	229	0.12	<10	211	<10	5	115
39	S07-18689	0.2	5.70	20	290	<5	3.06	<1	27	353	83	5.89	1.60	<10	3.20	833	18	0.93	111	950	34	5	<20	198	0.11	<10	223	<10	5	120
40	S07-18690	0.6	4.09	35	70	<5	3.15	2	24	494	104	6.59	1.47	10	1.64	685	45	0.47	127	570	38	10	<20	150	0.08	<10	223	<10	6	156
41	S07-18691	0.4	4.69	30	180	<5	5.76	1	22	498	58	5.34	1.45	<10	2.56	1349	23	0.55	126	1350	26	10	<20	224	0.06	<10	192	<10	7	108
42	S07-18692	0.2	5.44	20	190	<5	2.55	2	17	300	64	4.15	1.99	20	1.34	665	22	0.62	74	690	36	5	<20	124	0.11	<10	129	<10	7	123
43	S07-18693	0.4	4.15	20	140	<5	2.66	2	18	137	99	4.66	1.48	10	1.24	769	35	0.32	90	710	24	<5	<20	116	0.07	<10	220	<10	4	171
44	S07-18694	0.2	3.47	20	330	<5	4.20	<1	16	400	82	3.09	1.31	<10	3.52	1305	<1	0.62	122	330	14	5	<20	262	0.03	<10	61	<10	8	76
45	S07-18695	0.4	4.59	10	305	<5	2.64	<1	15	103	80	2.75	1.17	20	2.01	1092	<1	0.71	44	360	20	<5	<20	179	0.07	<10	31	<10	4	38
46	S07-18696	0.2	5.07	25	265	<5	2.61	<1	27	362	30	3.66	1.19	10	4.01	1568	<1	0.87	169	520	20	5	<20	199	0.08	<10	71	<10	5	138
47	S07-18697	0.4	3.56	10	130	<5	2.19	<1	16	115	104	4.45	0.60	<10	1.66	1154	14	1.08	45	390	24	<5	<20	159	0.05	<10	35	<10	4	60
48	S07-18698	0.4	3.44	15	265	<5	2.16	<1	15	119	74	2.53	0.92	10	1.55	1475	<1	0.60	53	350	14	<5	<20	145	0.05	<10	39	<10	4	34
49	S07-18699	0.2	5.11	10	600	<5	1.95	<1	10	54	25	2.69	1.69	10	1.68	1936	<1	0.46	25	350	18	<5	<20	118	0.09	<10	28	<10	4	51
50	S07-18700	0.8	4.72	100	260	<5	0.24	<1	7	26	27	2.85	3.18	<10	0.28	170	3	0.20	15	510	20	45	<20	50	0.35	<10	63	<10	11	47
51	S07-18701	0.2	3.36	10	345	<5	1.97	<1	13	94	45	2.66	1.10	<10	1.28	1932	<1	0.38	43	300	14	<5	<20	110	0.06	<10	33	<10	3	55
52	S07-18702	<0.2	4.86	10	580	<5	2.27	<1	8	55	53	2.14	1.79	20	1.09	2394	<1	0.78	31	450	20	<5	<20	119	0.11	<10	40	<10	5	49
53	S07-18703	0.4	3.84	15	195	<5	2.37	<1	15	85	79	3.28	1.29	20	1.14	1637	<1	0.47	50	410	18	<5	<20	113	0.07	<10	48	<10	4	68
54	S07-18704	0.4	5.28	35	285	<5	4.26	1	28	361	75	5.80	1.68	10	3.16	2199	16	0.47	186	1140	26	10	<20	191	0.08	<10	200	<10	6	177
55	S07-18705	0.6	5.06	20	135	<5	4.01	3	20	155	98	5.62	1.89	20	1.94	1266	25	0.23	87	1380	28	5	<20	175	0.12	<10	261	<10	8	251
56	S07-18706	0.8	4.51	35	170	<5	3.58	2	18	225	75	4.80	1.80	10	2.45	1087	21	0.27	110	970	32	10	<20	151	0.08	<10	231	<10	6	175
57	S07-18707	0.8	4.37	20	125	<5	2.42	2	18	169	82	5.26	1.81	<10	1.66	728	31	0.16	97	950	34	10	<20	108	0.07	<10	228	<10	5	202
58	S07-18708	1.2	4.23	25	120	<5	3.02	3	20	167	70	5.60	1.68	10	1.80	842	24	0.17	102	1180	34	10	<20	131	0.09	<10	262	<10	5	245
59	S07-18709	0.2	3.59	60	155	<5	3.65	1	27	631	37	4.94	1.06	<10	4.82	1434	13	0.45	260	500	18	10	<20	195	0.04	<10	125	<10	4	163
60	S07-18710	<0.2	0.05	<5	15	<5	>10	<1	<1	3	3	0.04	<0.01	<10	1.62	26	<1	<0.01	38	50	<2	<5	<20	5963	<0.01	<10	<1	<10	<1	3
61	S07-18711	0.4	5.21	60	350	<5	3.96	1	29	672	45	5.27	1.75	10	4.82	1604	6	0.43	241	820	26	15	<20	206	0.08	<10	188	<10	5	146
62	S07-18712	0.6	5.36	40	450	<5	3.22	<1	19	253	63	3.16	1.80	<10	2.42	977	6	0.21	113	500	24	10	<20	141	0.11	<10	81	<10	4	99
63	S07-18713	1.0	4.63	20	180	<5	3.99	1	18	159	62	4.59	1.89	20	2.05	1079	24	0.14	82	840	32	10	<20	178	0.09	<10	188	<10	7	119
64	S07-18714	0.4	4.51	15	525	<5	2.05	<1	17	97	105	3.26	1.85	10	2.12	819	3	0.16	51	550	26	5	<20	124	0.10	<10	82	<10	5	123
65	S07-18715	0.4	4.60	25	215	<5	4.59	2	16	319	57	4.44	1.66	10	2.81	1374	14	0.14	114	740	30	10	<20	191	0.07	<10	152	<10	6	166

Et #.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
66	S07-18716	1.2	5.08	40	175	<5	3.85	2	18	133	69	4.65	2.15	20	2.04	1026	18	0.21	81	1100	46	5	<20	196	0.11	<10	174	<10	8	150
67	S07-18717	1.2	4.17	25	140	<5	4.51	2	16	158	72	4.65	1.82	10	1.99	1153	22	0.13	82	860	42	10	<20	185	0.07	<10	177	<10	7	155
68	S07-18718	4.7	4.30	120	225	<5	0.45	2	11	38	571	5.30	2.24	10	1.81	419	7	0.25	26	590	116	50	<20	77	0.29	<10	53	<10	11	681
69	S07-18719	1.4	4.90	20	180	<5	4.08	3	17	301	76	5.27	1.87	20	1.66	1169	29	0.10	88	1180	56	15	<20	156	0.11	<10	231	<10	6	245
70	S07-18720	1.4	3.99	15	120	<5	2.51	2	14	323	60	4.23	2.03	20	1.28	707	25	0.11	63	1030	48	15	<20	128	0.09	<10	236	<10	6	212
71	S07-18721	2.4	5.06	20	130	<5	3.44	4	17	467	101	5.69	1.98	20	1.44	1003	32	0.11	78	1320	76	20	<20	144	0.12	<10	264	<10	7	327
72	S07-18722	3.0	5.06	25	150	<5	3.42	3	17	347	77	5.51	2.08	20	1.51	953	36	0.13	81	1220	86	20	<20	144	0.11	<10	271	<10	7	301
73	S07-18723	2.4	5.14	25	145	<5	3.20	3	18	547	80	5.67	2.12	20	1.38	907	33	0.13	82	1270	86	20	<20	130	0.13	<10	260	<10	7	259
74	S07-18724	2.2	4.84	25	110	<5	3.54	3	18	346	103	5.78	2.05	20	1.48	1001	32	0.12	81	1170	76	15	<20	141	0.12	<10	237	<10	7	283
75	S07-18725	0.6	6.86	15	255	<5	4.33	2	14	385	35	4.46	2.11	20	1.65	1297	11	0.43	44	1220	44	10	<20	178	0.17	<10	151	<10	8	165
76	S07-18726	0.6	5.15	15	145	<5	3.65	2	17	262	60	4.99	2.09	20	1.53	1015	21	0.26	62	1130	34	10	<20	161	0.13	<10	208	<10	8	215
77	S07-18727	0.4	4.39	15	135	<5	2.35	3	15	646	66	4.80	2.06	20	1.05	651	27	0.12	70	1170	40	10	<20	118	0.12	<10	260	<10	7	297
78	S07-18728	0.4	5.64	15	220	<5	3.85	<1	11	177	73	3.51	1.92	10	1.81	903	5	0.60	28	960	32	<5	<20	215	0.13	<10	143	<10	10	106
79	S07-18729	0.2	6.16	15	495	<5	3.24	<1	10	133	60	3.64	1.81	10	1.93	885	2	1.05	18	820	28	<5	<20	202	0.14	<10	107	<10	8	74
80	S07-18730	<0.2	6.84	10	885	<5	2.71	<1	8	149	42	2.72	2.10	10	1.78	834	2	1.57	18	870	28	<5	<20	191	0.16	<10	134	<10	8	81
81	S07-18731	0.2	6.33	15	565	<5	3.28	<1	11	146	47	3.10	2.07	10	1.74	906	3	1.39	21	690	26	<5	<20	194	0.14	<10	126	<10	9	93
82	S07-18732	0.2	5.91	50	500	<5	1.97	<1	10	190	57	3.54	2.09	10	1.66	601	9	0.94	21	630	26	<5	<20	142	0.13	<10	129	<10	7	104
83	S07-18733	0.4	5.45	35	185	<5	2.47	<1	13	223	71	4.58	1.85	10	1.33	696	9	0.99	29	560	42	5	<20	137	0.13	<10	137	<10	8	96
84	S07-18734	<0.2	5.61	15	810	<5	2.29	<1	8	260	44	2.83	1.79	10	1.38	609	5	1.25	24	550	20	<5	<20	137	0.14	<10	155	<10	6	109
85	S07-18735	<0.2	5.13	10	815	<5	1.93	<1	7	124	40	2.43	1.77	10	1.39	556	4	1.26	21	520	20	<5	<20	134	0.13	<10	150	<10	6	99
86	S07-18736	<0.2	4.75	15	400	<5	2.52	1	8	361	43	2.95	1.32	10	1.26	621	9	0.83	23	480	26	5	<20	146	0.11	<10	117	<10	5	121
87	S07-18737	<0.2	5.13	<5	985	<5	1.88	<1	8	168	51	2.79	1.53	10	1.39	515	6	0.98	20	460	20	<5	<20	121	0.13	<10	106	<10	6	89
88	S07-18738	<0.2	6.93	20	490	<5	2.37	<1	12	241	55	3.83	2.07	10	1.47	614	10	1.20	25	750	30	<5	<20	156	0.18	<10	161	<10	7	61
89	S07-18739	<0.2	7.13	10	1055	<5	2.08	<1	14	239	59	4.28	1.64	10	2.21	744	2	1.61	21	850	34	<5	<20	186	0.17	<10	170	<10	8	79
90	S07-18740	0.2	6.31	10	1195	<5	1.49	<1	10	338	51	3.35	1.63	10	1.64	654	3	1.66	21	650	24	<5	<20	152	0.15	<10	131	<10	6	69
91	S07-18741	0.4	5.88	10	900	<5	1.26	<1	10	138	42	3.31	1.72	20	1.42	540	3	1.92	18	630	26	<5	<20	156	0.15	<10	124	<10	6	64
92	S07-18742	0.8	5.46	15	120	<5	1.13	<1	12	427	62	4.57	1.77	10	1.25	475	6	1.76	26	530	32	5	<20	130	0.13	<10	113	<10	7	82
93	S07-18743	0.2	6.45	10	830	<5	3.37	<1	6	243	34	2.90	1.40	20	1.59	1031	3	1.10	18	560	28	<5	<20	174	0.13	<10	95	<10	8	86
94	S07-18744	0.4	5.62	10	465	<5	2.39	<1	7	144	56	2.43	1.52	20	1.36	662	3	0.96	17	480	30	<5	<20	160	0.13	<10	103	<10	8	78
95	S07-18745	0.8	6.44	25	230	<5	3.05	<1	17	261	88	4.47	1.32	10	1.78	772	10	0.30	31	1010	34	5	<20	192	0.19	<10	221	<10	10	118
96	S07-18746	0.6	5.33	20	410	<5	2.19	<1	13	394	96	3.94	1.15	<10	1.50	741	<1	1.55	21	680	24	5	<20	255	0.20	<10	147	<10	5	43
97	S07-18747	0.8	8.04	15	735	<5	3.06	<1	17	101	112	5.05	1.44	<10	1.87	1001	<1	3.52	22	980	36	<5	<20	412	0.27	<10	152	<10	5	64
98	S07-18748	4.6	4.28	110	205	<5	0.45	1	10	32	581	5.13	2.20	10	1.65	379	7	0.25	23	530	100	50	<20	69	0.25	<10	50	<10	10	672
99	S07-18749	0.6	7.95	15	1020	<5	2.82	<1	17	283	62	4.90	1.62	10	1.61	965	<1	3.10	21	960	34	<5	<20	399	0.31	<10	156	<10	6	52
100	S07-18750	<0.2	7.64	15	1465	<5	3.56	<1	23	185	54	5.94	1.49	<10	2.43	1178	<1	2.51	39	1010	30	<5	<20	504	0.28	<10	217	<10	7	58
101	S07-18751	0.2	5.49	15	590	<5	3.02	<1	15	230	62	4.34	1.35	<10	1.56	833	<1	1.60	26	790	20	<5	<20	295	0.21	<10	175	<10	5	48
102	S07-18752	0.4	7.66	15	535	<5	3.81	<1	23	122	90	6.15	1.51	10	2.31	1131	<1	2.93	37	1200	30	<5	<20	459	0.30	<10	219	<10	7	60
103	S07-18753	0.6	7.65	20	915	<5	4.24	<1	23	170	106	6.19	1.58	10	2.32	1151	<1	2.52	40	1290	34	<5	<20	447	0.30	<10	245	<10	8	74
104	S07-18754	0.2	7.46	20	890	<5	3.83	<1	20	148	73	5.26	1.51	10	2.17	1082	<1	2.42	33	1130	32	<5	<20	428	0.32	<10	248	<10	7	64
105	S07-18755	<0.2	0.07	<5	20	<5	>10	<1	<1	4	<1	0.41	0.02	<10	9.51	143	<1	0.02	4	150	2	<5	<20	1254	<0.01	<10	2	<10	<1	8

Et #.	Ta	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	W	Y	Zn	
106	S07-18756	0.4	7.69	20	1500	<5	3.29	<1	18	78	73	5.49	1.95	10	2.89	963	<1	2.15	30	1180	30	<5	<20	374	0.21	<10	210	<10	6	58
107	S07-18757	0.6	8.55	15	1610	<5	3.03	<1	27	57	102	6.17	1.79	10	2.87	1100	<1	3.33	29	1260	30	<5	<20	389	0.24	<10	209	<10	6	67
108	S07-18758	0.8	7.93	15	1635	<5	3.46	<1	22	70	85	5.85	2.18	10	2.84	1279	<1	2.79	30	1200	34	<5	<20	419	0.18	<10	198	<10	6	57
109	S07-18759	0.6	7.89	30	1565	<5	4.13	<1	20	85	95	5.98	2.05	10	3.06	1385	<1	2.33	28	1120	32	<5	<20	421	0.15	<10	205	<10	6	53
110	S07-18760	0.6	8.53	15	1220	<5	4.28	<1	24	71	96	6.45	1.81	10	3.05	1606	<1	2.78	29	1180	36	<5	<20	448	0.21	<10	188	<10	7	83
111	S07-18761	0.4	8.11	15	930	<5	4.33	<1	18	80	69	5.30	1.96	10	2.98	1316	<1	3.29	28	1110	34	<5	<20	447	0.17	<10	196	<10	6	57
112	S07-18762	0.2	8.06	20	590	<5	3.43	<1	21	57	89	5.38	1.65	10	2.84	1179	<1	3.19	29	890	32	<5	<20	332	0.22	<10	166	<10	5	77
113	S07-18763	0.4	7.56	15	505	<5	4.04	<1	23	77	67	6.11	1.56	10	3.33	1440	<1	4.00	33	1470	34	<5	<20	410	0.19	<10	224	<10	6	79
114	S07-18764	0.4	7.34	10	680	<5	3.56	<1	20	59	73	5.67	1.95	10	3.04	1396	<1	3.28	21	1040	30	<5	<20	359	0.20	<10	183	<10	5	61
115	S07-18765	<0.2	7.33	10	1180	<5	3.62	<1	15	107	65	5.49	2.12	10	2.86	1408	<1	2.30	25	1040	34	<5	<20	348	0.19	<10	152	<10	7	64
116	S07-18766	0.4	7.64	10	1190	<5	4.01	<1	19	187	61	5.37	2.08	10	2.57	1462	<1	2.26	29	1180	34	<5	<20	345	0.22	<10	153	<10	8	62
117	S07-18767	0.4	5.98	25	1650	<5	2.67	<1	17	299	81	4.91	2.28	10	2.61	1163	<1	0.35	42	800	32	5	<20	299	0.17	<10	144	<10	9	95
118	S07-18768	0.8	5.33	95	275	<5	3.35	<1	16	534	85	4.34	2.18	20	1.61	931	10	0.21	78	640	34	10	<20	294	0.16	<10	156	<10	10	157
119	S07-18769	1.8	5.78	45	220	<5	3.57	<1	20	422	83	5.33	2.20	20	1.48	884	13	0.21	95	680	54	5	<20	272	0.18	<10	133	<10	10	150
120	S07-18770	0.6	4.56	35	665	<5	3.22	<1	13	443	63	3.23	2.04	20	1.22	873	2	0.16	65	590	36	5	<20	223	0.18	<10	68	<10	7	102
121	S07-18771	0.4	5.59	55	390	<5	3.00	<1	15	369	36	3.90	2.16	20	1.07	1128	2	0.21	99	760	36	10	<20	193	0.19	<10	76	<10	7	136
122	S07-18772	0.4	4.72	25	745	<5	6.33	<1	8	238	43	2.89	2.16	20	1.14	1818	<1	0.31	68	580	30	<5	<20	415	0.12	<10	57	40	8	98
123	S07-18773	0.4	5.10	25	650	<5	3.25	<1	14	410	56	3.75	2.18	30	1.22	1152	3	0.31	78	750	28	5	<20	235	0.18	<10	90	<10	7	160
124	S07-18774	0.4	4.42	20	735	<5	3.37	<1	8	255	88	2.78	2.30	20	1.52	1104	<1	0.21	56	580	24	<5	<20	306	0.15	<10	80	<10	9	98
125	S07-18775	0.4	5.68	15	800	<5	4.28	<1	8	295	62	3.27	2.56	20	1.48	1366	<1	0.30	39	820	32	5	<20	288	0.17	<10	73	<10	9	92
126	S07-18776	4.6	4.55	55	675	<5	2.91	2	10	421	124	2.81	2.09	20	1.31	1046	9	0.16	76	580	34	5	<20	271	0.19	<10	195	<10	8	225
127	S07-18777	0.8	3.51	75	600	<5	2.57	<1	13	674	50	2.79	1.70	20	1.27	1347	2	0.33	86	360	26	10	<20	266	0.18	<10	75	<10	8	73
128	S07-18778	0.4	3.70	20	605	<5	2.35	<1	10	804	38	2.67	1.70	20	1.21	1379	2	0.46	72	470	22	10	<20	233	0.18	<10	61	<10	8	69
129	S07-18779	0.4	4.23	20	670	<5	2.34	<1	12	607	72	2.64	1.96	20	1.48	1515	2	0.63	79	500	30	10	<20	265	0.18	<10	72	<10	7	107
130	S07-18780	<0.2	0.06	<5	20	<5	>10	<1	<1	5	<1	0.49	0.04	<10	>10	177	<1	0.02	2	210	4	<5	<20	57	<0.01	<10	2	<10	<1	12
131	S07-18781	1.0	4.42	20	740	<5	1.60	<1	13	416	42	2.92	2.07	20	1.69	2204	2	0.49	73	470	28	5	<20	218	0.18	<10	85	<10	9	101
132	S07-18782	0.8	4.91	45	795	<5	1.73	<1	15	276	102	3.24	2.21	20	1.91	3090	1	0.57	186	470	28	<5	<20	201	0.18	<10	92	<10	7	178
133	S07-18783	1.2	4.37	50	725	<5	1.95	<1	18	222	117	2.91	2.08	20	1.88	3333	<1	0.65	189	420	24	<5	<20	244	0.18	<10	85	<10	7	108
134	S07-18784	1.0	4.23	40	695	<5	1.88	<1	15	301	142	2.77	1.97	20	1.78	3236	<1	0.60	154	390	20	<5	<20	234	0.17	<10	81	<10	6	106
135	S07-18785	1.0	5.39	60	955	<5	1.38	<1	18	313	178	4.09	2.54	30	1.95	4227	<1	0.61	172	440	36	<5	<20	180	0.20	<10	95	<10	9	166
136	S07-18786	1.2	5.23	55	555	<5	1.10	<1	18	353	120	4.36	2.47	30	1.53	3616	<1	0.63	122	430	36	5	<20	135	0.18	<10	94	<10	8	85
137	S07-18787	0.8	6.29	40	1200	<5	1.14	<1	18	181	147	3.31	2.97	30	1.87	3619	<1	0.79	169	540	38	<5	<20	147	0.24	<10	104	<10	7	114
138	S07-18788	1.0	7.20	55	1210	<5	1.16	<1	21	214	165	3.99	2.84	30	1.88	4014	<1	0.77	190	600	44	<5	<20	134	0.27	<10	106	<10	9	139
139	S07-18789	0.6	4.67	30	895	<5	1.13	<1	11	178	93	2.89	2.46	20	1.75	2705	<1	0.38	109	370	24	<5	<20	142	0.19	<10	88	<10	7	85
140	S07-18790	1.0	4.77	50	810	<5	1.43	<1	19	585	89	3.18	2.27	20	1.58	2253	2	0.27	183	480	30	10	<20	151	0.19	<10	90	<10	7	140
141	S07-18791	0.6	4.18	40	785	<5	1.51	<1	16	625	69	3.42	2.23	20	1.76	1974	2	0.26	115	400	28	10	<20	189	0.16	<10	92	<10	8	96
142	S07-18792	0.4	3.94	10	620	<5	1.46	<1	10	465	42	2.47	1.71	30	1.04	968	1	0.69	34	490	24	10	<20	161	0.18	<10	54	<10	6	49
143	S07-18793	0.2	3.83	5	630	<5	1.22	<1	6	428	103	2.18	1.67	30	0.95	420	3	0.86	20	480	20	5	<20	143	0.18	<10	47	<10	6	75
144	S07-18794	0.9	5.47	115	380	<5	0.25	<1	8	25	31	3.13	4.31	10	0.31	176	3	0.20	16	550	22	45	<20	55	0.39	<10	72	<10	11	46
145	S07-18795	0.2	6.38	10	1115	<5	2.35	<1	11	546	57	3.81	2.68	30	1.66	839	2	0.96	37	740	36	10	<20	239	0.21	<10	79	<10	8	77


Et #.	Ta	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	W	Y	Zn	
146	S07-18796	0.6	7.31	15	1235	<5	3.23	<1	14	213	52	3.81	2.66	30	1.90	1102	4	0.75	45	790	38	<5	<20	295	0.27	<10	93	<10	9	68
147	S07-18797	0.4	4.09	20	695	<5	3.54	<1	10	285	50	2.71	2.09	20	1.83	1630	<1	0.41	59	660	26	5	<20	376	0.14	<10	70	<10	8	92
148	S07-18798	0.4	3.49	15	625	<5	2.65	<1	9	474	62	2.29	1.86	20	1.37	1276	<1	0.38	44	410	20	5	<20	310	0.16	<10	55	<10	9	28
149	S07-18799	0.2	2.58	<5	370	<5	1.54	<1	3	285	14	1.34	1.04	30	0.67	645	<1	0.57	14	430	18	<5	<20	158	0.20	<10	31	<10	8	33
150	S07-18800	<0.2	3.01	<5	440	<5	1.71	<1	4	435	20	1.74	1.29	20	0.81	759	1	0.47	17	430	18	5	<20	174	0.17	<10	36	<10	7	38
151	S07-18801	0.6	4.83	40	960	<5	2.34	1	14	604	121	3.11	2.35	20	1.56	2026	7	0.21	105	430	32	10	<20	260	0.19	<10	159	<10	9	158
152	S07-18802	0.8	5.71	35	955	<5	2.47	2	17	590	103	3.89	2.25	30	1.61	2225	9	0.24	129	480	42	10	<20	256	0.22	<10	189	<10	9	224
153	S07-18803	0.8	6.10	40	465	<5	2.00	1	28	191	90	4.47	2.54	30	1.58	2765	1	0.32	174	460	42	<5	<20	212	0.20	<10	109	<10	6	148
154	S07-18804	0.4	4.69	30	1015	<5	2.00	<1	12	280	96	2.51	2.03	30	1.40	2350	<1	0.32	94	330	26	<5	<20	249	0.17	<10	92	<10	6	87
155	S07-18805	1.0	4.58	25	590	<5	2.07	3	14	374	262	2.80	2.16	30	1.57	1881	19	0.17	118	420	26	<5	<20	262	0.18	<10	300	<10	8	293
156	S07-18806	0.8	5.11	25	1050	<5	2.74	5	10	321	184	2.67	2.26	20	1.58	2310	39	0.14	139	580	28	<5	<20	267	0.22	<10	445	<10	8	563
157	S07-18807	1.0	5.40	20	285	<5	2.01	3	20	425	62	4.21	2.42	30	1.44	1688	17	0.23	121	520	44	5	<20	212	0.20	<10	290	<10	7	290
158	S07-18808	0.2	4.90	20	965	<5	1.95	<1	13	358	58	2.75	2.58	20	1.56	1477	2	0.48	71	510	30	5	<20	211	0.20	<10	92	<10	7	115
159	S07-18809	0.8	3.98	15	595	<5	2.17	<1	12	349	39	2.27	2.04	20	1.19	853	1	0.62	46	450	26	<5	<20	228	0.17	<10	62	<10	7	40
160	S07-18810	0.6	3.29	5	605	<5	1.50	<1	5	454	64	1.47	1.52	20	0.73	617	3	0.54	20	370	18	5	<20	141	0.16	<10	39	<10	5	28
161	S07-18811	0.2	2.98	<5	545	<5	1.40	<1	4	183	26	1.28	1.38	20	0.69	626	<1	0.77	11	370	16	<5	<20	126	0.17	<10	32	<10	4	18
162	S07-18812	0.4	3.21	5	595	<5	1.45	<1	5	259	24	1.50	1.45	20	0.72	662	<1	0.83	14	390	16	<5	<20	132	0.18	<10	33	<10	5	22
163	S07-18813	0.4	4.46	20	910	<5	2.29	<1	12	339	63	2.57	2.29	20	1.33	1886	2	0.46	85	450	26	5	<20	218	0.21	<10	85	<10	6	102
164	S07-18814	0.4	4.77	25	995	<5	2.22	<1	18	268	74	3.23	2.30	30	1.67	2167	<1	0.48	136	490	30	<5	<20	222	0.22	<10	93	<10	6	118
165	S07-18815	1.0	4.83	20	250	<5	1.75	<1	15	393	76	3.82	2.20	30	1.24	1332	1	0.72	62	530	34	5	<20	185	0.22	<10	81	<10	7	96
166	S07-18816	0.4	5.74	15	1060	<5	2.30	<1	11	288	89	3.38	2.02	30	1.52	1217	2	0.75	56	700	30	<5	<20	195	0.31	<10	126	<10	7	97
167	S07-18817	0.6	5.35	15	975	<5	2.68	<1	13	251	124	4.02	2.00	20	1.95	988	<1	1.05	46	550	36	<5	<20	229	0.26	<10	120	<10	7	101
168	S07-18818	0.2	4.96	30	880	<5	2.71	<1	9	259	91	2.78	2.21	20	1.45	925	1	0.75	68	640	24	<5	<20	190	0.23	<10	90	<10	7	107
169	S07-18819	0.2	4.19	20	730	<5	2.79	<1	9	327	82	2.70	2.06	20	1.33	794	1	0.47	64	540	22	5	<20	176	0.19	<10	75	<10	7	96
170	S07-18820	<0.2	0.05	<5	15	<5	>10	<1	<1	<1	1	0.42	0.02	<10	>10	140	<1	0.01	3	150	<2	<5	<20	1426	<0.01	<10	3	<10	<1	12
171	S07-18821	0.6	4.11	40	515	<5	2.54	<1	10	305	95	2.78	1.38	20	1.23	589	1	0.51	66	470	24	<5	<20	155	0.20	<10	78	<10	8	107
172	S07-18822	0.6	3.93	25	680	<5	2.56	<1	9	212	73	2.49	1.50	20	1.17	716	<1	0.53	60	500	20	<5	<20	154	0.20	<10	68	<10	7	82
173	S07-18823	0.4	4.30	25	450	<5	2.54	<1	12	198	87	2.63	1.46	20	1.23	721	<1	0.57	70	550	22	<5	<20	158	0.22	<10	89	<10	7	96
174	S07-18824	0.6	5.30	35	220	<5	3.31	2	16	288	104	4.01	1.31	20	1.65	1105	29	0.60	108	640	28	<5	<20	240	0.28	<10	331	<10	10	293
175	S07-18825	1.0	4.61	25	325	<5	3.13	1	10	296	79	3.30	1.61	30	1.61	1105	27	0.66	65	760	32	<5	<20	217	0.23	<10	173	<10	10	160
176	S07-18826	0.4	4.06	25	670	<5	2.62	<1	10	222	96	2.52	1.50	20	1.46	764	<1	0.54	66	510	22	<5	<20	191	0.21	<10	83	<10	8	99
177	S07-18827	0.2	4.76	30	715	<5	2.99	2	10	166	90	2.94	1.65	20	1.62	1017	24	0.46	91	550	24	<5	<20	191	0.26	<10	235	<10	8	224
178	S07-18828	4.8	4.32	135	305	<5	0.49	1	11	37	583	5.35	2.18	10	1.88	385	7	0.23	22	530	102	45	<20	80	0.27	<10	56	<10	12	675
179	S07-18829	0.4	4.45	25	690	<5	2.41	<1	9	210	57	2.78	1.63	20	1.71	849	4	0.56	73	470	30	<5	<20	182	0.24	<10	105	<10	8	118
180	S07-18830	0.2	3.93	25	620	<5	2.47	<1	8	192	62	2.11	1.54	20	1.62	968	3	0.43	71	370	26	<5	<20	192	0.20	<10	115	<10	7	121
181	S07-18831	0.2	4.33	30	705	<5	1.90	1	9	214	65	2.69	1.58	20	1.89	923	2	0.46	90	440	28	<5	<20	164	0.22	<10	112	<10	7	136
182	S07-18832	0.4	4.43	20	715	<5	2.30	4	8	281	82	2.99	1.54	20	1.84	975	48	0.32	82	530	30	<5	<20	213	0.23	<10	445	<10	10	395
183	S07-18833	0.4	4.54	35	530	<5	1.78	2	13	252	59	3.24	1.61	20	1.60	734	10	0.27	94	460	32	<5	<20	163	0.22	<10	171	<10	6	171
184	S07-18834	0.4	4.75	20	755	<5	1.73	1	10	322	81	3.00	1.72	30	1.79	863	4	0.42	89	480	26	<5	<20	173	0.26	<10	129	<10	7	145
185	S07-18835	1.0	4.67	25	210	<5	1.77	2	15	222	111	3.75	1.92	20	1.64	812	15	0.33	85	440	60	<5	<20	162	0.24	<10	207	<10	8	206

Et #.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	W	Y	Zn	
186	S07-18836	0.6	4.19	25	300	<5	1.62	2	11	204	64	3.18	1.69	20	1.54	738	9	0.30	90	420	38	<5	<20	154	0.22	<10	219	<10	7	179
187	S07-18837	0.6	4.54	45	190	<5	1.72	6	12	275	38	3.82	1.55	20	1.30	710	55	0.17	105	500	40	<5	<20	155	0.23	<10	481	<10	10	503
188	S07-18838	0.4	4.15	20	680	<5	2.03	1	9	190	94	2.24	1.61	20	1.46	800	6	0.11	60	410	28	<5	<20	220	0.21	<10	191	<10	8	135
189	S07-18839	0.8	4.21	25	350	<5	1.32	<1	12	289	51	3.02	1.63	20	1.38	608	2	0.13	58	330	28	5	<20	130	0.20	<10	90	<10	6	101
190	S07-18840	0.4	5.01	30	670	<5	3.07	<1	7	124	54	2.72	1.51	20	1.89	1319	<1	0.51	83	460	26	<5	<20	271	0.26	<10	84	<10	10	102
191	S07-18841	0.6	4.62	20	710	<5	1.56	<1	7	365	43	2.49	1.44	20	1.68	873	<1	0.42	58	400	20	<5	<20	160	0.24	<10	83	<10	6	88
192	S07-18842	<0.2	4.01	10	650	<5	1.15	<1	8	219	56	2.46	1.52	20	1.54	552	<1	0.29	39	330	22	<5	<20	120	0.20	<10	82	<10	6	61
193	S07-18843	0.4	4.21	20	655	<5	1.17	<1	10	357	57	2.89	1.39	20	1.48	574	2	0.29	44	350	24	<5	<20	121	0.20	<10	83	<10	6	84
194	S07-18844	0.4	4.61	25	675	<5	1.58	3	10	262	104	2.52	1.48	20	1.43	639	10	0.12	74	860	26	<5	<20	161	0.24	<10	177	<10	9	323
195	S07-18845	0.6	4.21	25	645	<5	1.43	2	9	319	74	2.41	1.23	20	1.40	616	9	0.11	62	610	24	5	<20	155	0.22	<10	173	<10	7	250
196	S07-18846	1.0	4.40	30	270	<5	2.85	1	11	302	207	2.89	1.46	20	1.63	1309	4	0.24	65	500	22	<5	<20	271	0.21	<10	96	<10	8	97
197	S07-18847	0.6	3.83	20	305	<5	1.30	<1	12	521	61	3.15	1.42	20	1.25	621	3	0.31	48	380	24	10	<20	133	0.20	<10	79	<10	7	84
198	S07-18848	1.0	3.49	35	550	<5	1.14	7	9	352	96	2.36	1.62	20	1.22	560	<1	0.21	61	260	112	5	<20	121	0.16	<10	68	<10	5	562
199	S07-18849	0.6	4.34	20	530	<5	1.42	<1	10	414	81	3.04	1.52	30	1.36	682	8	0.22	78	360	22	5	<20	125	0.21	<10	102	<10	6	94
200	S07-18850	0.2	3.83	15	590	<5	2.22	<1	6	436	44	2.32	1.55	20	1.49	1066	2	0.26	50	340	16	5	<20	184	0.20	<10	82	<10	8	70
201	S07-18851	0.4	4.60	30	420	<5	2.23	2	13	348	136	3.63	1.35	20	1.57	843	12	0.13	99	570	22	5	<20	165	0.22	<10	187	<10	7	181
202	S07-18852	<0.2	0.07	<5	15	<5	>10	<1	<1	4	<1	0.46	0.03	<10	>10	151	<1	0.01	3	140	<2	<5	<20	980	<0.01	<10	3	<10	<1	9
203	S07-18853	0.4	4.75	20	360	<5	2.71	2	11	279	151	3.59	1.50	20	1.79	1044	15	0.15	73	680	22	<5	<20	209	0.20	<10	249	<10	7	205
204	S07-18854	0.6	4.60	30	110	<5	2.68	2	19	381	47	4.31	1.41	20	1.65	801	18	0.18	87	770	32	5	<20	201	0.20	<10	244	<10	7	152
205	S07-18855	0.8	4.47	20	120	<5	1.78	2	17	337	46	4.41	1.73	20	1.38	635	18	0.14	87	770	34	<5	<20	134	0.22	<10	250	<10	7	185
206	S07-18856	0.4	3.80	15	500	<5	2.54	<1	8	332	33	2.61	1.61	20	1.46	1046	1	0.14	36	360	20	5	<20	191	0.18	<10	86	<10	5	59
207	S07-18857	1.2	3.49	25	150	<5	2.69	<1	18	265	110	3.98	1.49	20	1.47	1128	2	0.19	72	370	50	<5	<20	201	0.16	<10	103	<10	5	94
208	S07-18858	0.4	3.98	15	550	<5	2.04	<1	9	354	154	2.39	1.46	20	1.44	813	2	0.15	55	370	18	5	<20	161	0.20	<10	99	<10	6	111
209	S07-18859	0.6	4.49	20	645	<5	2.59	1	8	313	128	2.33	1.56	20	1.70	1188	3	0.24	58	410	18	<5	<20	214	0.23	<10	120	<10	8	102
210	S07-18860	1.0	3.92	20	85	<5	1.96	1	10	353	55	3.75	1.66	20	1.24	694	28	0.10	71	720	32	<5	<20	165	0.17	<10	160	<10	6	101
211	S07-18861	0.5	4.39	25	625	<5	2.53	3	10	417	39	3.00	2.25	20	1.47	785	44	0.11	88	500	24	5	<20	195	0.24	<10	445	<10	10	288
212	S07-18862	1.2	4.95	25	710	<5	2.89	6	19	282	55	4.27	2.65	30	1.69	894	100	0.10	123	840	40	<5	<20	226	0.28	<10	757	<10	10	551
213	S07-18863	0.8	5.74	100	510	<5	0.27	<1	7	26	33	3.36	4.15	10	0.31	164	3	0.09	14	500	22	40	<20	55	0.37	<10	73	<10	14	41
214	S07-18864	1.2	4.71	30	505	<5	3.78	4	22	280	26	5.58	2.57	30	1.76	1267	103	0.10	183	900	58	<5	<20	269	0.25	<10	796	<10	9	389
215	S07-18865	0.6	5.18	30	790	<5	3.82	4	12	364	29	3.23	2.62	30	1.84	1121	110	0.13	116	810	30	5	<20	269	0.27	<10	643	<10	12	377
216	S07-18866	0.8	5.33	20	760	<5	2.54	1	14	281	83	3.68	2.77	30	1.61	778	25	0.18	94	620	30	<5	<20	193	0.24	<10	257	<10	12	173
217	S07-18867	1.0	4.47	20	695	<5	2.30	4	11	575	45	3.20	2.52	30	1.51	752	41	0.09	109	470	26	10	<20	188	0.18	<10	555	<10	11	399
218	S07-18868	0.4	4.04	20	535	<5	3.26	1	16	568	37	3.51	2.00	30	1.58	1229	2	0.18	83	440	22	10	<20	214	0.16	<10	98	<10	10	132
219	S07-18869	0.8	4.48	25	675	<5	2.62	2	12	390	79	3.34	2.39	30	1.53	819	3	0.13	106	470	26	5	<20	191	0.20	<10	149	<10	12	176
220	S07-18870	0.6	4.98	30	670	<5	3.29	2	13	506	95	3.62	2.32	20	1.51	971	20	0.09	94	580	24	10	<20	208	0.19	<10	236	<10	9	197
221	S07-18871	0.6	5.00	20	790	<5	3.09	1	7	292	92	2.53	2.56	20	1.45	900	14	0.10	53	640	22	5	<20	205	0.20	<10	209	<10	10	171
222	S07-18872	0.4	5.10	20	840	<5	3.52	<1	9	233	68	2.61	2.54	30	1.50	1248	1	0.21	56	700	22	<5	<20	218	0.23	<10	119	<10	12	95
223	S07-18873	0.6	4.64	20	695	<5	3.01	<1	12	414	98	3.50	2.38	30	1.24	1260	7	0.31	60	670	22	10	<20	177	0.18	<10	118	<10	8	90
224	S07-18874	0.6	4.89	15	710	<5	5.42	1	10	228	40	3.47	2.38	30	1.54	2723	<1	0.79	37	940	26	<5	<20	328	0.21	<10	93	50	12	137
225	S07-18875	1.0	4.24	25	645	<5	2.26	<1	10	339	68	2.98	2.18	20	1.10	564	2	0.32	66	470	22	<5	<20	154	0.15	<10	87	<10	7	98
226	S07-18876	1.2	4.84	15	690	<5	3.15	<1	14	271	71	3.79	2.34	20	1.38	818	1	0.34	74	560	30	<5	<20	183	0.17	<10	82	<10	9	94
227	S07-18877	1.0	4.52	10	730	<5	2.97	<1	11	194	79	3.22	2.38	20	1.45	838	<1	0.28	68	460	30	<5	<20	182	0.14	<10	71	<10	7	75
228	S07-18878	1.0	5.17	15	870	<5	2.48	<1	8	326	102	2.80	2.68	20	1.37	580	1	0.49	71	490	24	5	<20	145	0.15	<10	80	<10	7	101

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
QC DATA:																															
Repeat:																															
1	S07-18651	0.2	5.62	60	290	<5	3.77	<1	27	401	74	5.38	1.20	<10	3.68	1726	<1	1.24	133	920	36	10	<20	241	0.10	<10	164	<10	5	107	
10	S07-18660	<0.2	5.54	15	365	<5	2.93	<1	21	168	99	3.61	1.21	20	1.52	1423	<1	1.38	59	480	40	<5	<20	208	0.12	<10	111	<10	7	72	
19	S07-18669	0.2	4.75	90	120	<5	4.33	<1	48	939	63	6.44	0.67	<10	6.91	1073	6	1.13	437	780	28	15	<20	266	0.06	<10	159	<10	5	166	
37	S07-18687	0.4	5.14	30	225	<5	4.59	<1	29	403	79	5.98	1.31	<10	3.41	1067	17	1.02	137	930	32	5	<20	245	0.10	<10	196	<10	8	93	
45	S07-18695	0.4	4.33	10	300	<5	2.43	<1	13	108	81	2.64	1.13	10	1.97	1022	<1	0.70	39	340	20	<5	<20	173	0.07	<10	30	<10	4	35	
54	S07-18704	0.4	4.98	45	290	<5	3.97	1	26	358	74	5.53	1.66	10	3.15	2090	15	0.48	177	1060	26	5	<20	190	0.09	<10	201	<10	6	156	
71	S07-18721	2.4	4.80	20	115	<5	3.46	3	16	432	97	5.35	1.98	20	1.36	939	29	0.11	70	1280	66	15	<20	134	0.11	<10	250	<10	6	335	
80	S07-18730	<0.2	6.94	10	880	<5	2.59	<1	8	160	45	2.80	1.85	10	1.80	833	2	1.72	18	860	28	<5	<20	192	0.15	<10	137	<10	8	80	
89	S07-18739	<0.2	6.58	10	995	<5	2.11	<1	12	242	50	4.30	1.55	10	2.18	682	1	1.53	19	760	30	<5	<20	188	0.15	<10	173	<10	7	70	
106	S07-18756	0.4	7.80	15	1560	<5	3.26	<1	20	84	78	5.54	2.04	10	3.00	956	<1	2.33	30	1180	32	<5	<20	384	0.20	<10	215	<10	7	60	
115	S07-18765	0.2	7.32	5	1205	<5	3.67	<1	15	104	67	5.45	2.15	10	2.78	1425	<1	2.26	22	990	32	<5	<20	339	0.19	<10	157	<10	7	58	
124	S07-18774	0.4	4.48	15	775	<5	3.37	<1	9	258	97	3.00	2.25	20	1.61	1179	<1	0.23	55	580	22	<5	<20	322	0.18	<10	82	<10	9	104	
141	S07-18791	0.6	4.40	25	815	<5	1.50	<1	18	638	68	3.75	2.27	20	1.80	2006	2	0.26	118	450	30	10	<20	195	0.18	<10	94	<10	8	100	
150	S07-18800	<0.2	2.93	<5	455	<5	1.80	<1	4	453	20	1.69	1.32	20	0.84	728	1	0.48	16	420	18	5	<20	175	0.16	<10	35	<10	8	33	
159	S07-18809	0.4	3.99	25	650	<5	2.14	<1	12	330	36	2.27	1.93	20	1.15	855	1	0.59	52	500	26	5	<20	218	0.19	<10	58	<10	6	44	
176	S07-18826	0.4	4.11	20	650	<5	2.51	<1	11	213	97	2.70	1.58	20	1.43	789	<1	0.54	67	520	22	<5	<20	182	0.22	<10	83	<10	7	103	
185	S07-18835	1.0	5.04	30	210	<5	1.76	2	16	219	114	4.04	1.70	30	1.59	855	16	0.34	87	460	64	<5	<20	160	0.25	<10	205	<10	8	212	
194	S07-18844	0.6	4.31	20	640	<5	1.57	3	9	262	102	2.32	1.54	20	1.35	604	10	0.11	72	790	22	5	<20	150	0.22	<10	170	<10	8	330	
211	S07-18861	0.6	4.35	25	630	<5	2.47	3	10	424	41	2.97	2.30	20	1.45	763	43	0.11	86	490	24	5	<20	192	0.24	<10	452	<10	8	280	
220	S07-18870	0.8	4.90	30	665	<5	2.99	2	12	499	94	3.63	2.28	20	1.50	966	18	0.09	84	520	22	10	<20	207	0.19	<10	227	<10	10	196	
Resplit:																															
1	S07-18651	0.2	5.32	70	275	<5	3.72	<1	28	419	80	5.32	1.17	10	3.78	1743	<1	1.18	130	890	36	5	<20	245	0.09	<10	164	<10	6	104	
37	S07-18687	0.2	5.70	30	260	<5	5.15	<1	30	370	80	5.91	1.32	<10	3.58	1090	16	1.04	163	940	34	10	<20	256	0.11	<10	207	<10	8	100	
71	S07-18721	3.2	4.78	20	135	<5	3.24	3	16	464	98	5.31	2.00	20	1.34	948	31	0.11	74	1270	70	20	<20	148	0.12	<10	252	<10	6	320	
106	S07-18756	0.4	7.43	15	1615	<5	3.12	<1	20	91	70	5.21	2.08	10	2.95	889	<1	2.53	28	1090	30	<5	<20	396	0.19	<10	228	<10	7	58	
141	S07-18791	0.6	4.38	25	795	<5	1.53	<1	16	621	71	3.36	1.92	20	1.81	2015	2	0.25	111	440	32	5	<20	188	0.18	<10	91	<10	7	110	
176	S07-18826	0.3	4.35	25	695	<5	2.76	<1	11	227	89	2.54	1.74	20	1.41	747	<1	0.59	71	510	22	<5	<20	188	0.23	<10	85	<10	7	102	
211	S07-18861	0.7	4.13	<5	575	<5	2.50	<1	9	453	40	2.99	2.32	20	1.44	748	1	0.14	86	490	24	5	<20	195	0.26	<10	435	<10	9	290	
Standard:																															
Stsd3		0.4	5.68	20	1280	<5	2.38	<1	15	59	36	4.28	1.41	30	1.21	2640	5	1.29	34	1660	52	5	<20	241	0.32	<10	103	<10	30	203	
Stsd3		0.5	5.59	20	1275	<5	2.62	<1	15	60	32	4.27	1.46	30	1.32	2555	5	1.20	34	1780	60	5	<20	259	0.33	<10	112	<10	28	200	
Stsd3		0.5	5.76	20	1260	<5	2.35	<1	14	60	31	4.12	1.33	30	1.30	2331	4	1.28	30	1710	54	<5	<20	261	0.29	<10	110	<10	27	202	
Stsd3		0.4	5.76	20	1375	<5	2.51	<1	15	61	36	4.30	1.37	40	1.22	2645	5	1.27	32	1610	60	<5	<20	263	0.33	<10	112	<10	31	206	
Stsd3		0.4	5.66	20	1370	<5	2.46	<1	15	63	37	4.33	1.39	40	1.26	2628	5	1.24	31	1710	60	<5	<20	247	0.33	<10	116	<10	31	203	
Stsd3		0.5	5.58	20	1300	<5	2.43	<1	14	57	38	4.36	1.45	40	1.36	2338	5	1.30	30	1780	54	<5	<20	258	0.31	<10	112	<10	30	200	
Stsd3		0.4	5.49	25	1250	<5	2.44	<1	13	60	36	4.27	1.43	30	1.15	2555	6	1.29	32	1600	56	5	<20	268	0.19	<10	108	<10	6	210	

ICP: 4 ACID DIGEST/ICP-FINISH
 AG: 4 ACID DIGEST/AA-FINISH

Jutta Jealouse
 ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2268

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

4-Mar-08


Attention: Bob Singh

No. of samples received: 174
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-135
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-33681	<0.03	<0.001
2	S07-33682	<0.03	<0.001
3	S07-33683	<0.03	<0.001
4	S07-33684	<0.03	<0.001
5	S07-33685	<0.03	<0.001
6	S07-33686	<0.03	<0.001
7	S07-33687	<0.03	<0.001
8	S07-33688	<0.03	<0.001
9	S07-33689	0.11	0.003
10	S07-33690	0.22	0.007
11	S07-33691	0.57	0.017
12	S07-33692	0.13	0.004
13	S07-33693	0.05	0.002
14	S07-33694	0.17	0.005
15	S07-33695	* <0.03	<0.001
16	S07-33696	0.11	0.003
17	S07-33697	0.09	0.003
18	S07-33698	0.13	0.004
19	S07-33699	0.09	0.003
20	S07-33700	0.09	0.003
21	S07-33701	0.08	0.002
22	S07-33702	* 2.11	0.062
23	S07-33703	0.08	0.002
24	S07-33704	0.05	0.002
25	S07-33705	0.06	0.002
26	S07-33706	0.07	0.002
27	S07-33707	0.06	0.002
28	S07-33708	<0.03	<0.001

* = 30g FA


ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	S07-33709	<0.03	<0.001
30	S07-33710	<0.03	<0.001
31	S07-33711	0.06	0.002
32	S07-33712	0.13	0.004
33	S07-33713	0.18	0.005
34	S07-33714	0.22	0.006
35	S07-33715	0.26	0.007
36	S07-33716	0.23	0.007
37	S07-33717	0.19	0.006
38	S07-33718	0.12	0.004
39	S07-33719	0.08	0.002
40	S07-33720	<0.03	<0.001
41	S07-33721	<0.03	<0.001
42	S07-33722	<0.03	<0.001
43	S07-33723	<0.03	<0.001
44	S07-33724	<0.03	<0.001
45	S07-33725	0.09	0.003
46	S07-33726	0.13	0.004
47	S07-33727	0.24	0.007
48	S07-33728	0.20	0.006
49	S07-33729	0.22	0.006
50	S07-33730	0.14	0.004
51	S07-33731	0.17	0.005
52	S07-33732	1.10	0.032
53	S07-33733	0.50	0.015
54	S07-33734	* <0.03	<0.001
55	S07-33735	0.07	0.002
56	S07-33736	0.14	0.004
57	S07-33737	0.15	0.004
58	S07-33738	<0.03	<0.001
59	S07-33739	0.06	0.002
60	S07-33740	* 0.44	0.013
61	S07-33741	0.25	0.007
62	S07-33742	0.19	0.006
63	S07-33743	<0.03	<0.001
64	S07-33744	0.14	0.004
65	S07-33745	<0.03	<0.001
66	S07-33746	<0.03	<0.001
67	S07-33747	0.04	0.001
68	S07-33748	0.08	0.002
69	S07-33749	<0.03	<0.001
70	S07-33750	0.35	0.010
71	S07-33751	<0.03	<0.001

* = 30g FA



ECO TECH LABORATORY LTD.

 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
72	S07-33752	<0.03	<0.001
73	S07-33753	<0.03	<0.001
74	S07-33754	<0.03	<0.001
75	S07-33755	<0.03	<0.001
76	S07-33756	0.20	0.006
77	S07-33757	0.51	0.015
78	S07-33758	<0.03	<0.001
79	S07-33759	0.68	0.020
80	S07-33760	0.21	0.006
81	S07-33761	0.23	0.007
82	S07-33762	<0.03	<0.001
83	S07-33763	0.17	0.005
84	S07-33764	0.23	0.007
85	S07-33765	<0.03	<0.001
86	S07-33766	0.13	0.004
87	S07-33767	<0.03	<0.001
88	S07-33768	<0.03	<0.001
89	S07-33769	<0.03	<0.001
90	S07-33770	<0.03	<0.001
91	S07-33771	<0.03	<0.001
92	S07-33772	2.10	0.061
93	S07-33773	0.04	0.001
94	S07-33774	<0.03	<0.001
95	S07-33775	0.09	0.003
96	S07-33776	0.06	0.002
97	S07-33777	<0.03	<0.001
98	S07-33778	0.05	0.002
99	S07-33779	0.20	0.006
100	S07-33780	0.03	0.001
101	S07-33781	<0.03	<0.001
102	S07-33782	<0.03	<0.001
103	S07-33783	<0.03	<0.001
104	S07-33784	<0.03	<0.001
105	S07-33785	<0.03	<0.001
106	S07-33786	<0.03	<0.001
107	S07-33787	<0.03	<0.001
108	S07-33788	<0.03	<0.001
109	S07-33789	<0.03	<0.001
110	S07-33790	0.04	0.001
111	S07-33791	<0.03	<0.001
112	S07-33792	<0.03	<0.001
113	S07-33793	<0.03	<0.001
114	S07-33794	<0.03	<0.001

= 30g FA



ECO TECH LABORATORY LTD.

 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
115	S07-33795	0.07	0.002
116	S07-33796	0.21	0.006
117	S07-33797	0.60	0.017
118	S07-33798	* <0.03	<0.001
119	S07-33799	0.24	0.007
120	S07-33800	0.07	0.002
121	S07-33801	<0.03	<0.001
122	S07-33802	<0.03	<0.001
123	S07-33803	<0.03	<0.001
124	S07-33804	<0.03	<0.001
125	S07-33805	<0.03	<0.001
126	S07-33806	<0.03	<0.001
127	S07-33807	<0.03	<0.001
128	S07-33808	<0.03	<0.001
129	S07-33809	<0.03	<0.001
130	S07-33810	0.03	0.001
131	S07-33811	0.04	0.001
132	S07-33812	<0.03	<0.001
133	S07-33813	<0.03	<0.001
134	S07-33814	0.09	0.003
135	S07-33815	0.66	0.019
136	S07-33816	<0.03	<0.001
137	S07-33817	* 0.41	0.012
138	S07-33818	0.72	0.021
139	S07-33819	0.08	0.002
140	S07-33820	0.16	0.005
141	S07-33821	<0.03	<0.001
142	S07-33822	<0.03	<0.001
143	S07-33823	<0.03	<0.001
144	S07-33824	<0.03	<0.001
145	S07-33825	<0.03	<0.001
146	S07-33826	<0.03	<0.001
147	S07-33827	<0.03	<0.001
148	S07-33828	<0.03	<0.001
149	S07-33829	<0.03	<0.001
150	S07-33830	<0.03	<0.001
151	S07-33831	<0.03	<0.001
152	S07-33832	<0.03	<0.001
153	S07-33833	0.06	0.002
154	S07-33834	0.22	0.006
155	S07-33835	0.05	0.001
156	S07-33836	0.34	0.010
157	S07-33837	<0.03	<0.001

* = 30g FA



ECO TECH LABORATORY LTD.

 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
158	S07-33838	0.02	0.001
159	S07-33839	0.05	0.002
160	S07-33840	0.24	0.007
161	S07-33841	0.09	0.003
162	S07-33842	0.22	0.006
163	S07-33843	<0.03	<0.001
164	S07-33844	0.18	0.005
165	S07-33845	<0.03	<0.001
166	S07-33846	<0.03	<0.001
167	S07-33847	0.04	0.001
168	S07-33848	<0.03	<0.001
169	S07-33849	<0.03	<0.001
170	S07-33850	<0.03	<0.001
171	S07-33851	0.77	0.022
172	S07-33852	2.03	0.059
173	S07-33853	2.22	0.065
174	S07-33854	1.96	0.057

QC DATA:**Resplit:**

1	S07-33681	<0.03	<0.001
36	S07-33716	0.22	0.006
71	S07-33751	<0.03	<0.001
106	S07-33786	<0.03	<0.001
141	S07-33821	<0.03	<0.001

Standard:

OXI54	1.86	0.054
OXI54	1.90	0.055
OXI54	1.82	0.053
OXI54	1.88	0.055
OXI54	1.89	0.055
OXI54	1.84	0.054
OXI54	1.89	0.055
OXI54	1.88	0.055
OXI54	1.84	0.054
OXI54	1.90	0.055
OXI54	1.88	0.055
OXI54	1.90	0.055
OXI54	1.87	0.055
OXI54	1.88	0.055

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

J/nw
LS/07


ECO TECH LABORATORY LTD.

 Jutta Jealous
 B.C. Certified Assayer

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS 2007-2268

Skygold Ventures
615 - 800 W. Pender Street
Vancouver, BC
V6B 2V6

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 174

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-135

Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-33681	0.3	5.56	35	410	<5	2.74	<1	14	167	75	3.45	1.31	20	1.36	2071	<1	1.41	59	570	38	<5	<20	205	0.11	<10	106	<10	6	95
2	S07-33682	0.3	5.51	15	445	<5	2.51	<1	21	117	60	3.91	1.47	10	2.08	1504	1	1.22	68	620	38	<5	<20	192	0.10	<10	102	<10	5	74
3	S07-33683	0.2	5.14	20	440	<5	3.73	<1	17	167	71	3.50	1.45	10	1.91	1961	1	1.05	62	490	36	<5	<20	220	0.08	<10	83	<10	6	87
4	S07-33684	0.6	5.01	10	215	<5	3.38	<1	16	72	88	4.37	1.44	20	1.53	2417	<1	1.26	38	1620	36	<5	<20	222	0.11	<10	112	<10	7	117
5	S07-33685	0.4	4.91	10	355	<5	1.91	<1	17	62	78	4.08	1.30	20	1.41	1550	<1	1.01	48	580	32	<5	<20	152	0.10	<10	73	<10	5	81
6	S07-33686	0.6	4.83	10	300	<5	1.77	<1	23	56	102	3.71	1.35	10	1.25	1421	<1	1.03	46	580	38	<5	<20	151	0.10	<10	74	<10	4	70
7	S07-33687	0.6	5.77	5	615	<5	1.75	<1	10	65	53	3.05	2.11	10	1.43	1233	<1	0.75	27	320	32	<5	<20	138	0.10	<10	67	<10	5	68
8	S07-33688	0.3	4.95	20	405	<5	3.08	<1	21	159	63	3.85	1.71	20	1.92	1931	<1	0.66	69	510	34	<5	<20	180	0.07	<10	76	<10	5	77
9	S07-33689	0.4	4.96	20	435	<5	3.62	<1	16	207	81	3.29	1.71	20	1.71	1869	<1	0.58	79	460	32	<5	<20	164	0.09	<10	65	<10	6	67
10	S07-33690	0.6	4.71	5	565	<5	2.78	<1	13	130	189	2.40	2.01	20	1.49	1388	12	0.45	33	520	26	<5	<20	159	0.08	<10	71	<10	6	68
11	S07-33691	0.7	4.41	10	145	<5	2.18	<1	21	160	67	3.53	1.57	30	0.95	718	1	0.62	57	1390	38	<5	<20	116	0.10	<10	93	<10	8	91
12	S07-33692	0.6	4.86	15	185	<5	2.85	<1	22	88	77	3.78	1.56	20	1.13	1060	17	0.53	64	980	46	<5	<20	124	0.10	<10	92	<10	6	110
13	S07-33693	0.4	6.06	15	210	<5	2.93	<1	16	112	53	4.19	2.15	20	1.31	1159	29	0.87	65	450	40	<5	<20	126	0.12	<10	130	<10	7	133
14	S07-33694	0.7	5.44	15	120	<5	2.40	1	20	132	73	4.21	2.09	20	1.08	824	32	0.80	76	580	40	5	<20	107	0.11	<10	132	<10	6	143
15	S07-33695	<0.2	7.09	<5	495	<5	2.56	<1	10	82	37	4.29	1.16	10	1.35	770	3	3.01	28	820	32	<5	<20	380	0.35	<10	108	<10	18	50
16	S07-33696	0.8	3.84	10	145	<5	1.81	<1	18	103	59	2.74	1.47	20	0.80	578	5	0.48	45	480	42	<5	<20	77	0.08	<10	87	<10	4	95
17	S07-33697	1.3	4.08	25	125	<5	2.86	<1	23	96	61	4.06	1.44	20	1.10	1050	42	0.76	65	1140	70	10	<20	143	0.08	<10	99	<10	7	90
18	S07-33698	1.2	4.93	15	205	<5	2.55	<1	14	128	45	3.30	2.08	20	1.27	777	23	1.18	49	460	44	<5	<20	147	0.09	<10	97	<10	7	96
19	S07-33699	0.6	5.22	10	220	<5	6.42	1	12	55	49	3.14	1.78	20	1.04	1177	22	1.12	49	400	38	<5	<20	247	0.09	<10	111	<10	8	116
20	S07-33700	0.6	3.79	15	130	<5	>10	2	13	68	56	4.10	1.29	20	0.79	1439	34	0.67	56	520	34	5	<20	355	0.06	<10	119	<10	8	156
21	S07-33701	0.4	6.13	10	175	<5	5.62	<1	11	63	48	3.20	2.21	20	1.04	1330	21	1.15	40	330	42	<5	<20	183	0.09	<10	97	<10	8	100
22	S07-33702	4.7	4.18	135	290	<5	0.44	1	10	35	615	5.08	2.39	10	1.76	353	7	0.31	22	500	98	45	<20	75	0.25	<10	53	<10	11	656
23	S07-33703	0.4	6.72	10	250	<5	4.08	1	13	89	51	3.19	2.36	20	1.17	851	22	1.56	47	460	38	5	<20	159	0.10	<10	107	<10	7	117
24	S07-33704	0.3	5.03	15	165	<5	5.64	<1	18	122	47	3.79	1.90	20	1.91	1122	25	0.65	67	620	36	<5	<20	181	0.06	<10	141	<10	7	105
25	S07-33705	0.6	7.05	15	580	<5	3.31	1	17	68	45	3.65	2.17	20	1.62	931	22	0.81	62	450	48	<5	<20	137	0.12	<10	95	<10	7	152

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
26	S07-33706	0.6	5.87	10	105	<5	1.76	2	18	103	63	6.90	2.29	20	0.92	452	51	0.45	86	630	48	5	<20	90	0.09	<10	147	<10	6	183
27	S07-33707	0.2	4.13	20	115	<5	2.82	1	21	168	68	5.07	1.64	10	1.66	658	48	0.21	100	650	30	10	<20	166	0.07	<10	200	<10	6	118
28	S07-33708	<0.2	6.11	25	310	<5	3.09	<1	22	342	130	5.40	2.47	<10	3.27	899	21	0.46	106	950	40	5	<20	206	0.11	<10	237	<10	7	125
29	S07-33709	<0.2	6.47	70	205	<5	3.91	<1	30	243	111	6.11	2.68	<10	3.44	922	13	0.52	140	1130	36	<5	<20	203	0.09	<10	228	<10	6	119
30	S07-33710	<0.2	5.15	85	215	<5	3.54	<1	33	369	134	5.81	2.10	10	3.45	983	23	0.36	332	760	30	10	<20	179	0.07	<10	204	<10	5	117
31	S07-33711	0.2	4.31	55	235	<5	3.47	<1	22	416	48	4.96	2.00	20	3.64	952	21	0.21	171	770	24	10	<20	184	0.05	<10	191	<10	6	129
32	S07-33712	1.0	4.36	35	150	<5	2.99	2	20	309	83	4.72	2.10	20	2.67	835	25	0.18	135	870	38	15	<20	147	0.06	<10	215	<10	6	178
33	S07-33713	1.6	4.59	45	130	<5	3.29	2	16	247	67	4.81	2.16	20	1.93	832	25	0.16	86	970	58	15	<20	171	0.07	<10	229	<10	7	177
34	S07-33714	2.3	4.26	20	105	<5	3.08	2	15	203	70	4.24	2.04	20	1.71	839	26	0.14	73	960	62	15	<20	162	0.06	<10	239	<10	5	219
35	S07-33715	2.0	4.81	35	125	<5	3.40	2	18	266	62	5.15	2.26	20	1.85	906	27	0.17	91	1020	66	15	<20	198	0.07	<10	234	<10	8	179
36	S07-33716	2.6	4.57	30	145	<5	3.10	2	16	204	60	4.70	2.29	20	1.83	818	24	0.18	82	940	62	15	<20	191	0.07	<10	244	<10	7	160
37	S07-33717	2.0	4.85	65	130	<5	3.73	1	19	391	70	5.14	2.23	20	2.05	1027	29	0.18	103	990	58	15	<20	207	0.07	<10	236	<10	7	149
38	S07-33718	1.4	4.72	40	135	<5	3.53	2	22	466	59	5.29	2.19	20	2.62	1079	26	0.19	135	960	50	15	<20	180	0.06	<10	219	<10	6	210
39	S07-33719	0.7	4.52	85	190	<5	3.69	2	27	681	64	5.15	2.02	20	3.79	1240	18	0.26	210	780	32	15	<20	197	0.06	<10	195	<10	6	201
40	S07-33720	<0.2	4.21	155	240	<5	3.46	1	33	894	34	4.82	1.67	<10	5.92	1589	7	0.47	334	600	18	15	<20	229	0.04	<10	132	<10	5	193
41	S07-33721	<0.2	3.45	35	310	<5	3.46	<1	15	462	39	3.30	1.34	<10	3.74	1498	9	0.26	131	490	16	10	<20	229	0.05	<10	91	<10	6	87
42	S07-33722	0.2	5.26	20	655	<5	1.70	<1	4	107	37	1.66	2.23	10	1.50	782	<1	0.40	16	310	16	<5	<20	121	0.08	<10	32	<10	6	49
43	S07-33723	<0.2	4.85	165	215	<5	2.99	<1	26	496	48	4.25	1.53	10	4.26	1699	<1	0.91	188	590	20	10	<20	209	0.07	<10	88	<10	5	134
44	S07-33724	<0.2	4.16	45	150	<5	3.92	<1	37	763	34	5.04	1.51	<10	5.82	1852	<1	0.60	254	610	22	10	<20	231	0.05	<10	115	<10	5	132
45	S07-33725	1.2	4.26	50	180	<5	3.40	2	22	436	49	4.76	1.88	10	3.08	1214	17	0.14	157	660	40	10	<20	200	0.05	<10	164	<10	7	179
46	S07-33726	2.0	4.55	15	100	<5	2.66	3	16	247	70	4.54	2.21	20	1.57	818	29	0.14	77	1050	58	15	<20	142	0.07	<10	260	<10	7	228
47	S07-33727	2.4	4.51	20	85	<5	2.59	3	15	234	83	4.57	2.07	20	1.40	829	31	0.11	68	1070	74	15	<20	129	0.07	<10	245	<10	6	241
48	S07-33728	2.2	4.57	20	110	<5	2.75	3	17	237	81	4.68	2.23	20	1.52	893	29	0.14	71	1000	72	15	<20	142	0.07	<10	257	<10	6	226
49	S07-33729	1.6	4.44	20	105	<5	2.58	2	15	318	94	4.38	1.95	20	1.36	869	26	0.10	64	990	64	15	<20	143	0.08	<10	226	<10	6	207
50	S07-33730	1.8	4.84	20	165	<5	2.82	2	16	200	67	5.01	2.05	20	1.55	844	28	0.16	76	1010	48	10	<20	188	0.08	<10	245	<10	8	218
51	S07-33731	0.6	5.04	15	110	<5	2.82	2	14	181	49	4.87	2.04	20	1.60	846	28	0.15	67	1070	38	10	<20	180	0.09	<10	226	<10	8	188
52	S07-33732	0.2	6.25	20	445	<5	2.80	1	13	167	121	3.94	2.23	20	1.83	725	12	0.30	41	830	38	5	<20	192	0.13	<10	246	<10	8	153
53	S07-33733	0.8	7.82	20	850	<5	4.04	1	16	299	65	3.71	2.53	10	1.62	934	9	0.38	51	1780	78	5	<20	222	0.19	<10	175	<10	10	216
54	S07-33734	<0.2	0.09	<5	20	5	>10	<1	<1	4	1	0.50	0.04	<10	>10	192	<1	0.02	3	180	4	<5	<20	320	<0.01	<10	4	<10	<1	15
55	S07-33735	<0.2	5.86	10	805	<5	2.59	<1	7	160	58	2.61	2.40	20	1.29	698	19	0.84	12	840	32	<5	<20	186	0.14	<10	109	<10	8	91
56	S07-33736	<0.2	5.51	15	525	<5	2.08	<1	9	231	52	3.25	2.20	10	1.01	619	4	0.60	14	840	38	5	<20	125	0.16	<10	79	<10	7	73
57	S07-33737	<0.2	6.32	10	305	<5	3.10	<1	12	157	101	3.99	2.93	20	1.66	1111	2	0.77	14	960	38	<5	<20	199	0.14	<10	116	<10	8	74
58	S07-33738	<0.2	6.38	15	900	<5	3.51	<1	13	194	73	4.35	2.33	20	1.72	1246	<1	0.74	13	1190	34	<5	<20	233	0.17	<10	110	<10	8	95
59	S07-33739	<0.2	7.38	10	1030	<5	2.71	<1	13	75	84	4.82	2.65	20	1.81	1197	<1	1.57	12	1460	42	<5	<20	241	0.19	<10	113	<10	7	79
60	S07-33740	0.8	5.71	100	395	<5	0.27	<1	7	24	30	3.50	4.64	10	0.30	162	3	0.15	16	500	20	40	<20	44	0.35	<10	67	<10	10	46
61	S07-33741	<0.2	5.99	25	360	<5	3.25	<1	13	262	22	4.33	2.11	20	1.38	1193	4	1.11	18	910	36	<5	<20	280	0.14	<10	81	<10	9	68
62	S07-33742	<0.2	6.30	25	660	<5	4.56	4	15	345	54	4.54	2.16	10	1.86	1321	<1	1.36	25	760	32	<5	<20	451	0.15	<10	130	<10	8	384
63	S07-33743	<0.2	6.47	20	545	<5	3.22	<1	17	95	64	4.36	2.65	10	2.03	1103	<1	1.77	27	600	26	<5	<20	341	0.15	<10	162	<10	5	65
64	S07-33744	<0.2	6.43	15	395	<5	3.48	<1	14	137	50	3.86	2.24	10	1.61	1069	<1	2.04	22	620	26	<5	<20	375	0.13	<10	127	<10	6	73
65	S07-33745	<0.2	6.88	10	460	<5	3.76	<1	14	72	50	4.17	1.61	10	1.93	1087	<1	2.20	21	760	26	<5	<20	590	0.16	<10	133	<10	6	60

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	g%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn	
66	S07-33746	<0.2	7.80	25	325	<5	4.45	<1	22	127	93	5.65	1.69	10	2.65	1206	<1	1.88	36	780	32	<5	<20	890	0.19	<10	206	<10	5	64
67	S07-33747	<0.2	7.07	15	545	<5	3.43	<1	16	119	62	4.35	1.89	10	1.89	1027	<1	1.95	24	630	26	<5	<20	517	0.17	<10	139	<10	5	52
68	S07-33748	<0.2	6.91	15	565	<5	3.05	<1	17	125	64	4.24	1.82	10	1.82	1012	<1	1.97	24	650	28	<5	<20	478	0.17	<10	131	<10	5	54
69	S07-33749	<0.2	6.74	5	550	<5	2.37	<1	12	138	94	3.88	1.96	20	1.50	878	<1	2.10	18	710	30	<5	<20	307	0.19	<10	102	<10	6	60
70	S07-33750	2.0	7.76	20	525	<5	3.04	<1	21	81	85	5.42	1.93	10	2.24	1331	<1	2.21	30	680	28	<5	<20	537	0.22	<10	192	<10	4	79
71	S07-33751	<0.2	5.95	10	555	<5	2.48	<1	11	169	54	3.29	1.28	20	1.28	847	<1	2.44	18	540	26	<5	<20	430	0.17	<10	86	<10	6	50
72	S07-33752	<0.2	7.42	10	625	<5	3.45	<1	14	85	59	4.62	1.66	10	2.02	1053	<1	1.98	24	680	28	<5	<20	569	0.21	<10	142	<10	5	56
73	S07-33753	<0.2	7.36	10	720	<5	3.24	<1	20	92	77	4.86	1.43	<10	2.23	1261	<1	2.30	28	620	28	<5	<20	651	0.20	<10	179	<10	4	70
74	S07-33754	<0.2	5.54	15	865	<5	2.72	<1	10	194	40	2.73	1.53	<10	1.12	690	2	1.53	20	410	24	<5	<20	340	0.18	<10	167	<10	5	35
75	S07-33755	0.2	7.49	25	820	<5	3.17	<1	17	131	104	4.68	1.85	10	1.69	766	5	2.63	34	730	32	<5	<20	364	0.22	<10	320	<10	6	77
76	S07-33756	0.4	6.57	20	335	<5	2.12	<1	17	150	74	4.15	2.05	20	1.13	565	1	2.00	31	580	50	<5	<20	208	0.20	<10	143	<10	8	45
77	S07-33757	0.4	7.67	25	320	<5	3.19	<1	19	205	132	5.21	1.97	10	1.59	829	6	2.37	35	870	40	<5	<20	307	0.20	<10	242	<10	7	56
78	S07-33758	<0.2	7.97	15	1050	<5	2.71	<1	19	87	69	5.23	2.11	10	2.10	1002	<1	2.21	24	970	34	<5	<20	335	0.21	<10	185	<10	5	74
79	S07-33759	0.4	7.44	15	795	<5	3.47	<1	18	216	142	5.59	1.99	10	1.90	1106	<1	1.60	20	1280	34	<5	<20	330	0.25	<10	198	<10	8	80
80	S07-33760	1.2	7.53	10	585	<5	3.62	<1	20	371	373	6.92	1.93	20	1.67	1131	1	2.06	17	2020	128	5	<20	398	0.33	<10	214	<10	12	73
81	S07-33761	0.7	7.52	<5	470	<5	3.73	<1	20	86	211	6.53	1.83	20	1.76	1162	1	2.67	12	1930	36	<5	<20	438	0.33	<10	219	<10	11	72
82	S07-33762	<0.2	0.07	<5	15	<5	>10	<1	<1	<1	1	0.48	0.03	<10	>10	187	<1	0.02	1	200	<2	<5	<20	100	<0.01	<10	2	<10	<1	12
83	S07-33763	0.2	7.23	10	745	<5	3.23	<1	16	105	122	5.18	1.97	20	1.83	1076	1	2.11	20	1140	32	<5	<20	352	0.24	<10	185	<10	7	73
84	S07-33764	<0.2	7.26	10	655	<5	4.63	<1	11	163	42	4.45	2.02	20	1.57	1289	1	1.56	14	1100	30	<5	<20	393	0.24	<10	112	<10	7	73
85	S07-33765	<0.2	6.48	10	640	<5	4.02	<1	11	112	48	4.24	1.91	10	1.37	1072	<1	1.53	14	1130	30	<5	<20	318	0.22	<10	110	<10	7	45
86	S07-33766	<0.2	7.19	10	835	<5	3.51	<1	13	111	64	4.73	1.44	10	1.65	1029	<1	1.52	19	930	38	<5	<20	375	0.22	<10	164	<10	5	82
87	S07-33767	<0.2	6.81	5	605	<5	3.22	<1	11	74	34	4.13	1.09	10	1.42	1062	<1	2.11	13	860	26	<5	<20	482	0.19	<10	107	<10	6	69
88	S07-33768	<0.2	6.50	<5	560	<5	2.97	<1	8	79	26	3.44	1.01	20	1.07	876	<1	2.25	9	530	28	<5	<20	432	0.18	<10	82	<10	8	53
89	S07-33769	<0.2	6.93	5	515	<5	2.79	<1	13	84	57	4.45	0.97	10	1.52	931	<1	2.80	17	650	30	<5	<20	495	0.23	<10	132	<10	4	75
90	S07-33770	<0.2	8.07	10	655	<5	3.47	<1	18	90	70	5.25	1.11	<10	1.92	1165	<1	3.26	17	780	32	<5	<20	597	0.29	<10	178	<10	5	66
91	S07-33771	0.2	7.95	10	780	<5	3.25	<1	16	88	71	5.13	1.04	<10	1.86	1110	<1	2.91	17	880	28	<5	<20	403	0.26	<10	180	<10	5	63
92	S07-33772	4.8	4.33	130	335	<5	0.44	1	10	34	598	5.02	2.23	10	1.75	375	7	0.30	23	520	100	50	<20	71	0.26	<10	55	<10	11	678
93	S07-33773	<0.2	6.77	<5	850	<5	2.73	<1	10	180	53	3.78	0.91	10	1.27	868	<1	2.58	13	710	26	<5	<20	351	0.21	<10	109	<10	6	50
94	S07-33774	<0.2	6.58	<5	515	<5	2.52	<1	13	54	51	4.02	1.25	10	1.34	866	<1	2.54	12	710	26	<5	<20	284	0.21	<10	127	<10	5	64
95	S07-33775	<0.2	7.05	<5	765	<5	2.75	<1	15	57	64	4.34	0.95	10	1.50	911	<1	2.39	15	760	28	<5	<20	280	0.23	<10	151	<10	5	52
96	S07-33776	0.3	7.21	5	650	<5	2.84	<1	15	97	71	4.49	1.27	10	1.49	1041	<1	2.10	15	930	26	<5	<20	300	0.22	<10	148	<10	6	55
97	S07-33777	<0.2	7.52	5	460	<5	3.05	<1	16	52	90	4.78	1.05	<10	1.61	1134	<1	2.86	14	870	28	<5	<20	321	0.24	<10	159	<10	5	67
98	S07-33778	0.2	7.41	5	390	<5	2.60	<1	13	68	57	4.24	1.21	10	1.34	997	<1	3.84	14	880	34	<5	<20	392	0.23	<10	123	<10	7	62
99	S07-33779	0.6	7.00	10	635	<5	2.94	15	9	116	80	3.67	1.15	10	1.20	736	<1	3.16	12	760	34	<5	<20	397	0.20	<10	90	<10	7	1351
100	S07-33780	0.4	4.52	15	100	<5	1.80	3	17	293	123	5.02	1.06	20	0.71	355	94	1.88	84	720	28	<5	<20	191	0.13	<10	295	<10	8	266
101	S07-33781	0.2	6.58	15	310	<5	3.09	1	25	129	94	5.64	1.48	20	2.36	819	6	3.15	56	1190	38	<5	<20	328	0.18	<10	274	<10	8	135
102	S07-33782	<0.2	5.85	10	745	<5	3.01	<1	25	144	58	5.84	1.76	<10	3.67	1136	<1	1.84	57	870	26	<5	<20	283	0.18	<10	228	<10	5	69
103	S07-33783	<0.2	7.28	20	785	<5	3.40	<1	28	154	61	6.31	1.23	<10	3.78	1234	<1	1.95	64	900	32	<5	<20	316	0.20	<10	235	<10	7	74
104	S07-33784	<0.2	7.06	10	615	<5	3.64	<1	28	121	62	6.11	1.13	<10	3.36	1260	<1	2.16	51	900	26	<5	<20	340	0.19	<10	214	<10	5	58
105	S07-33785	<0.2	6.99	15	480	<5	3.77	<1	24	106	76	6.04	0.92	<10	3.24	1217	<1	3.11	43	890	28	<5	<20	442	0.19	<10	223	<10	5	59

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La ...g%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
106	S07-33786	<0.2	7.63	10	535	<5	3.87	<1	23	66	89	6.06	1.00	<10	2.71	1177	<1	3.76	27	760	28	<5	<20	494	0.18	<10	208	<10	5	62
107	S07-33787	0.2	7.63	5	255	<5	3.69	<1	24	72	104	5.98	0.92	<10	2.74	1160	<1	3.30	30	1100	28	<5	<20	389	0.17	<10	222	<10	4	62
108	S07-33788	0.2	7.93	10	575	<5	4.11	<1	24	66	117	6.12	1.08	<10	2.63	1187	<1	3.03	28	830	30	<5	<20	434	0.17	<10	228	<10	4	56
109	S07-33789	<0.2	7.94	5	500	<5	3.48	<1	21	59	95	6.24	1.02	<10	2.57	1167	<1	2.83	26	890	28	<5	<20	359	0.16	<10	233	<10	4	56
110	S07-33790	<0.2	8.10	10	270	<5	3.79	<1	23	61	91	6.51	0.91	<10	2.68	1236	<1	2.80	28	800	30	<5	<20	338	0.18	<10	226	<10	4	59
111	S07-33791	<0.2	7.60	5	160	<5	3.63	<1	24	63	97	6.25	0.95	<10	2.66	1106	<1	3.66	26	880	26	<5	<20	392	0.17	<10	261	<10	5	67
112	S07-33792	0.2	7.73	5	390	<5	4.70	<1	21	61	110	5.95	0.99	<10	2.53	1180	<1	3.70	23	810	28	<5	<20	514	0.19	<10	218	<10	7	56
113	S07-33793	0.2	7.60	10	585	<5	3.71	<1	21	60	122	5.95	1.07	<10	2.52	1121	<1	2.41	25	870	32	<5	<20	396	0.20	<10	215	<10	5	64
114	S07-33794	0.2	7.64	10	520	<5	3.49	<1	19	65	103	5.83	1.13	10	2.27	1027	<1	3.76	32	910	26	<5	<20	465	0.20	<10	222	<10	5	72
115	S07-33795	0.4	8.61	10	780	<5	4.20	<1	23	56	102	6.48	1.27	<10	2.41	1190	<1	3.81	29	960	42	<5	<20	602	0.21	<10	241	<10	5	70
116	S07-33796	<0.2	8.22	15	650	<5	5.45	<1	19	55	77	5.60	1.00	10	2.42	1254	<1	3.59	23	1060	30	<5	<20	670	0.19	<10	182	<10	6	43
117	S07-33797	<0.2	7.74	20	360	<5	3.37	<1	19	88	49	5.02	1.32	10	1.75	888	<1	3.52	25	790	34	<5	<20	462	0.17	<10	170	<10	6	47
118	S07-33798	<0.2	0.08	<5	20	<5	>10	<1	<1	3	2	0.48	0.03	<10	>10	174	<1	0.02	2	260	<2	<5	<20	133	<0.01	<10	3	<10	<1	15
119	S07-33799	<0.2	6.78	10	920	<5	4.17	<1	13	72	84	4.02	1.09	<10	1.62	882	<1	3.79	16	890	34	<5	<20	514	0.15	<10	137	<10	7	64
120	S07-33800	0.4	7.18	10	1210	<5	3.57	<1	14	53	68	4.60	1.10	10	1.92	901	<1	4.41	18	890	26	<5	<20	498	0.22	<10	177	<10	6	44
121	S07-33801	<0.2	6.99	20	1250	<5	3.95	<1	24	127	171	6.19	1.05	10	2.99	1074	<1	2.83	61	1210	32	<5	<20	465	0.20	<10	284	<10	8	70
122	S07-33802	<0.2	6.94	15	780	<5	3.81	<1	26	146	111	6.46	0.98	10	3.36	1132	<1	3.04	67	1080	26	<5	<20	423	0.16	<10	227	<10	7	55
123	S07-33803	<0.2	7.44	10	105	<5	4.26	<1	27	146	63	6.62	0.23	10	3.60	1171	<1	4.23	67	1210	30	<5	<20	337	0.35	<10	236	<10	8	76
124	S07-33804	<0.2	7.55	5	530	<5	4.81	<1	29	156	208	6.68	0.45	10	3.26	1210	<1	4.33	76	1170	34	5	<20	297	0.31	<10	326	<10	10	62
125	S07-33805	0.2	7.40	5	725	<5	4.28	<1	30	143	204	6.75	0.74	10	2.91	1095	<1	3.79	72	1240	28	5	<20	331	0.23	<10	296	<10	9	68
126	S07-33806	<0.2	6.93	10	630	<5	5.21	<1	25	190	119	6.04	0.89	10	3.49	1181	<1	3.49	72	1100	30	5	<20	496	0.17	<10	235	<10	8	52
127	S07-33807	<0.2	6.54	15	505	<5	4.61	<1	33	377	100	6.63	0.94	<10	4.62	1133	<1	2.03	130	1040	28	25	<20	487	0.10	<10	221	<10	6	76
128	S07-33808	<0.2	6.23	15	870	<5	5.21	<1	32	378	99	6.43	0.91	<10	4.51	1176	<1	1.86	119	1020	26	25	<20	507	0.10	<10	209	<10	6	67
129	S07-33809	0.2	6.63	15	540	<5	4.62	<1	28	332	121	5.95	0.91	10	4.05	1000	<1	2.64	96	1140	24	10	<20	461	0.15	<10	202	<10	8	51
130	S07-33810	<0.2	6.58	15	550	<5	4.65	<1	28	338	87	5.95	0.90	10	4.23	1124	<1	2.90	99	1110	24	5	<20	400	0.13	<10	199	<10	7	62
131	S07-33811	<0.2	7.77	5	410	<5	3.38	<1	19	72	96	5.42	0.95	10	2.79	901	<1	4.21	28	1130	26	<5	<20	302	0.23	<10	219	<10	6	44
132	S07-33812	0.2	6.58	15	255	<5	2.07	<1	22	79	92	5.52	0.88	<10	2.64	993	<1	4.19	28	1080	22	<5	<20	230	0.18	<10	197	<10	4	72
133	S07-33813	<0.2	7.60	15	610	<5	4.25	<1	22	141	60	5.85	0.78	10	3.53	1562	<1	3.46	44	1180	26	<5	<20	372	0.14	<10	199	<10	6	65
134	S07-33814	<0.2	7.59	10	1515	<5	3.38	<1	21	96	56	5.89	1.50	10	3.41	1236	<1	1.11	35	1160	32	<5	<20	239	0.16	<10	199	<10	5	76
135	S07-33815	0.4	5.51	25	445	<5	3.09	<1	12	136	82	3.49	1.72	20	1.54	645	2	0.24	63	600	26	<5	<20	180	0.13	<10	128	<10	5	103
136	S07-33816	1.0	4.14	30	245	<5	2.92	<1	12	179	63	3.07	1.79	20	1.07	729	3	0.15	65	520	26	<5	<20	163	0.12	<10	77	<10	5	101
137	S07-33817	0.7	5.66	95	350	<5	0.26	<1	7	24	29	3.42	4.40	10	0.30	161	3	0.10	15	500	20	40	<20	45	0.35	<10	66	<10	11	45
138	S07-33818	0.4	4.53	30	295	<5	3.05	<1	11	170	82	2.96	1.80	20	1.16	788	2	0.17	76	530	22	<5	<20	181	0.15	<10	88	<10	6	151
139	S07-33819	<0.2	2.89	10	435	<5	2.84	<1	4	128	17	1.77	1.10	10	1.02	994	<1	0.10	26	350	14	<5	<20	178	0.09	<10	46	<10	4	87
140	S07-33820	0.2	4.91	10	255	<5	3.22	<1	9	184	31	2.83	1.45	30	1.31	580	<1	0.42	28	530	26	<5	<20	205	0.12	<10	57	<10	6	51
141	S07-33821	<0.2	3.63	5	475	<5	2.38	<1	5	188	13	1.54	1.17	20	0.88	393	<1	0.46	16	530	18	<5	<20	174	0.12	<10	34	<10	4	40
142	S07-33822	<0.2	3.52	5	400	<5	2.64	<1	5	227	10	1.44	1.06	20	0.82	343	<1	0.61	16	1150	26	<5	<20	200	0.13	<10	32	<10	6	37
143	S07-33823	<0.2	3.51	<5	390	<5	2.62	<1	4	161	7	1.42	0.90	30	0.89	333	<1	0.41	13	480	20	<5	<20	153	0.16	<10	28	<10	5	22
144	S07-33824	<0.2	3.79	<5	425	<5	3.89	<1	5	70	8	1.36	0.99	20	0.89	323	<1	0.84	10	410	18	<5	<20	234	0.12	<10	26	<10	5	26
145	S07-33825	<0.2	3.28	<5	355	<5	3.70	<1	4	97	8	1.27	0.89	20	0.86	326	<1	0.90	11	440	20	<5	<20	232	0.14	<10	25	<10	5	23

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La %	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
150	S07-33830	<0.2	3.40	<5	385	<5	2.99	<1	4	107	8	1.30	1.04	20	0.84	388	<1	1.16	11	420	18	<5	<20	188	0.16	<10	28	<10	5	24
159	S07-33839	0.6	4.12	40	585	<5	2.34	<1	11	188	44	2.69	1.02	20	1.58	2092	<1	0.18	82	390	22	<5	<20	207	0.14	<10	72	<10	5	87

Resplit:

1	S07-33681	0.4	5.72	45	430	<5	2.62	<1	16	170	82	3.76	1.36	20	1.45	2190	<1	1.48	68	570	40	<5	<20	221	0.12	<10	111	40	7	105
36	S07-33716	2.6	4.79	20	135	<5	3.36	2	17	200	60	4.96	2.11	20	1.81	869	27	0.17	86	1000	66	15	<20	187	0.08	<10	235	<10	8	160
71	S07-33751	0.2	5.86	<5	580	<5	2.33	<1	10	170	61	3.12	1.00	20	1.29	796	<1	2.44	18	540	24	<5	<20	410	0.16	<10	85	<10	5	56
106	S07-33786	<0.2	7.70	10	545	<5	3.90	<1	23	45	93	5.99	1.10	<10	2.77	1193	<1	3.56	27	770	30	<5	<20	494	0.16	<10	210	<10	4	64
141	S07-33821	0.2	3.64	5	465	<5	2.28	<1	6	170	13	1.50	1.38	20	0.85	379	<1	0.45	15	500	16	<5	<20	173	0.11	<10	32	<10	5	46


Standard:


Std3		0.5	5.53	20	1280	<5	2.28	<1	14	57	35	4.10	1.34	40	1.37	2471	5	1.42	33	1700	50	<5	<20	234	0.30	<10	103	<10	29	198
Std3		0.4	5.49	20	1275	<5	2.29	<1	14	59	35	4.15	1.40	40	1.38	2463	5	1.44	32	1780	50	<5	<20	231	0.31	<10	111	<10	29	207
Std3		0.4	5.61	20	1270	<5	2.25	<1	14	58	39	4.10	1.21	30	1.37	2487	5	1.41	32	1610	52	<5	<20	227	0.31	<10	113	<10	28	205
Std3		0.4	5.75	25	1280	<5	2.82	<1	15	58	34	4.18	1.23	30	1.40	2598	5	1.43	34	1750	54	<5	<20	234	0.32	<10	104	<10	29	222
Std3		0.4	5.58	20	1240	<5	2.48	<1	14	57	35	4.09	1.32	30	1.37	2530	5	1.41	32	1780	56	<5	<20	227	0.30	<10	103	<10	28	221

ICP: 4 ACID DIGEST/ICP-FINISH

AG: 4 ACID DIGEST/AA-FINISH

JJ/nw
 Jf/td2268as/td2268bs
 XLS/07


 ECO TECH LABORATORY LTD.
 Jutta Jealous
 E.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2269

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

27-Feb-08

Attention: Bob Singh

No. of samples received: 41

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-137

Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-33855	<0.03	<0.001
2	S07-33856	<0.03	<0.001
3	S07-33857	<0.03	<0.001
4	S07-33858	<0.03	<0.001
5	S07-33859	<0.03	<0.001
6	S07-33860	<0.03	<0.001
7	S07-33861	<0.03	<0.001
8	S07-33862	0.05	0.001
9	S07-33863	<0.03	<0.001
10	S07-33864	0.13	0.004
11	S07-33865	0.14	0.004
12	S07-33866	0.15	0.004
13	S07-33867	<0.03	<0.001
14	S07-33868	0.03	0.001
15	S07-33869	<0.03	<0.001
16	S07-33870	<0.03	<0.001
17	S07-33871	<0.03	<0.001
18	S07-33872	<0.03	<0.001
19	S07-33873	<0.03	<0.001
20	S07-33874	0.04	0.001
21	S07-33875	0.04	0.001
22	S07-33876	0.05	0.001
23	S07-33877	0.03	0.001
24	S07-33878	0.04	0.001
25	S07-33879	0.03	0.001
26	S07-33880	<0.03	<0.001
27	S07-33881	0.05	0.001
28	S07-33882	0.09	0.003
29	S07-33883	0.13	0.004
30	S07-33884	0.18	0.005

ECO TECH LABORATORY LTD.

Jutta Jealousse
B.C. Certified Assayer

* = 30g FA

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
31	S07-33885	0.25	0.007
32	S07-33886	0.21	0.006
33	S07-33887	0.10	0.003
34	S07-33888	1.38	0.040
35	S07-33889	* 0.41	0.012
36	S07-33890	0.28	0.008
37	S07-33891	0.24	0.007
38	S07-33892	0.14	0.004
39	S07-33893	<0.03	<0.001
40	S07-33894	0.07	0.002
41	S07-33895	0.27	0.008

QC DATA:

Resplit:

1	S07-33855	<0.03	<0.001
36	S07-33890	0.21	0.006


Standard:

OXI54	1.84	0.054
OXI54	1.83	0.053
OXI54	1.81	0.053

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw
XLS/07


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

ECO TECH LABORATORY LTD.

10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700

Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS . . . 2007-2269

Skygold Ventures

615 - 800 W. Pender Street
Vancouver, BC
V6B 2V6

No. of samples received: 41

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-137

Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-33855	0.3	4.91	35	715	<5	0.75	<1	11	80	22	1.64	2.02	10	0.86	1228	<1	0.72	38	310	18	<5	<20	70	0.11	<10	27	<10	5	35
2	S07-33856	0.4	4.68	20	790	<5	1.00	<1	6	66	48	2.02	2.19	10	1.08	1196	<1	0.58	18	260	22	<5	<20	81	0.11	<10	20	<10	4	49
3	S07-33857	0.4	5.37	95	865	<5	0.91	<1	11	75	52	2.77	2.21	10	0.74	863	1	0.26	42	320	24	<5	<20	67	0.12	<10	32	<10	5	45
4	S07-33858	<0.2	3.64	170	345	<5	2.07	<1	12	297	21	3.29	1.47	<10	1.21	1000	2	0.23	97	460	14	5	<20	116	0.07	<10	74	<10	4	66
5	S07-33859	0.4	4.43	195	195	<5	3.52	<1	22	557	18	4.48	1.51	<10	4.84	1324	<1	0.60	190	860	18	10	<20	189	0.06	<10	104	<10	5	63
6	S07-33860	1.1	4.67	205	235	<5	5.51	<1	27	806	37	5.33	2.01	<10	5.70	1510	<1	0.53	275	710	22	15	<20	296	0.04	<10	130	<10	5	70
7	S07-33861	0.6	5.74	130	330	<5	5.51	<1	25	426	53	5.72	2.13	<10	5.17	1622	<1	0.81	164	900	24	10	<20	307	0.08	<10	155	<10	5	66
8	S07-33862	0.4	5.79	50	765	<5	2.24	<1	8	172	61	2.71	2.48	20	0.89	964	5	0.39	34	690	28	<5	<20	112	0.13	<10	66	<10	7	30
9	S07-33863	0.3	5.23	45	675	<5	1.33	<1	8	257	58	3.34	2.23	10	1.16	1010	1	0.28	44	660	22	<5	<20	72	0.12	<10	54	<10	7	58
10	S07-33864	0.8	5.10	160	550	<5	1.38	<1	23	638	85	5.49	2.16	10	0.76	1751	5	0.28	129	650	40	10	<20	101	0.09	<10	111	<10	5	131
11	S07-33865	0.4	4.58	105	85	<5	2.22	2	22	224	105	5.90	1.78	20	1.21	863	26	0.15	95	940	34	<5	<20	139	0.07	<10	230	<10	6	149
12	S07-33866	3.2	5.01	110	100	<5	2.45	1	23	267	70	5.54	1.84	20	1.42	904	25	0.18	108	1100	60	<5	<20	138	0.08	<10	270	<10	6	120
13	S07-33867	<0.2	0.09	<5	15	<5	>10	<1	<1	2	1	0.51	0.04	<10	>10	167	<1	0.01	3	230	<2	<5	<20	55	<0.01	<10	4	<10	<1	15
14	S07-33868	0.6	4.35	85	395	<5	3.37	<1	22	590	73	4.56	1.98	20	2.53	1102	12	0.20	113	950	44	10	<20	205	0.06	<10	196	<10	6	104
15	S07-33869	0.4	4.48	65	430	<5	4.20	<1	25	897	60	5.11	2.07	10	5.38	1699	5	0.52	199	820	36	10	<20	263	0.05	<10	188	<10	5	109
16	S07-33870	0.6	3.94	90	235	<5	4.01	<1	32	865	26	5.51	1.40	10	6.34	2197	<1	0.54	233	550	30	15	<20	300	0.05	<10	104	<10	4	80
17	S07-33871	0.6	5.41	90	475	<5	2.94	<1	32	658	55	5.17	1.81	10	4.17	1806	1	0.82	196	720	26	10	<20	190	0.08	<10	136	<10	5	98
18	S07-33872	0.4	4.90	65	370	<5	2.84	<1	28	381	54	5.43	1.47	10	3.89	1787	<1	0.77	114	740	28	10	<20	225	0.08	<10	130	<10	4	100
19	S07-33873	1.1	4.03	85	390	<5	3.60	<1	30	838	64	4.78	1.75	20	3.97	1630	8	0.47	213	670	26	15	<20	294	0.05	<10	156	<10	5	126
20	S07-33874	0.7	4.56	35	90	<5	3.44	3	16	358	58	5.03	2.01	20	1.87	1141	25	0.20	85	1110	34	5	<20	197	0.07	<10	234	<10	8	199
21	S07-33875	1.0	5.03	45	160	<5	4.09	1	22	358	98	4.88	1.90	20	2.72	1314	20	0.41	106	900	32	5	<20	221	0.07	<10	246	<10	7	129
22	S07-33876	0.8	4.47	35	295	<5	6.01	1	18	526	65	3.98	1.96	20	2.86	1984	17	0.49	94	780	30	10	<20	293	0.06	<10	165	<10	6	127
23	S07-33877	1.0	4.49	35	255	<5	5.57	2	21	578	71	4.32	1.93	10	2.90	1925	18	0.44	118	760	32	10	<20	307	0.06	<10	179	<10	7	143
24	S07-33878	1.2	4.43	40	80	<5	2.56	3	18	232	67	5.13	2.13	20	1.71	856	30	0.22	101	980	32	5	<20	173	0.06	<10	253	<10	6	211
25	S07-33879	0.7	4.94	55	380	<5	2.92	<1	27	482	49	5.02	1.69	20	4.07	1227	14	0.54	165	880	36	5	<20	239	0.07	<10	199	<10	7	118

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn	
26	S07-33880	0.5	4.11	75	215	<5	4.66	<1	32	693	57	5.09	1.69	<10	6.22	1685	<1	0.49	238	630	22	10	<20	300	0.05	<10	117	<10	5	138
27	S07-33881	1.0	5.06	35	135	<5	4.05	2	22	232	88	4.56	1.75	20	2.46	1152	20	0.49	92	1060	42	5	<20	266	0.07	<10	234	<10	7	166
28	S07-33882	1.8	4.52	30	105	<5	3.92	3	21	347	130	4.62	2.01	20	2.36	1027	24	0.17	118	1010	56	10	<20	239	0.06	<10	237	<10	7	244
29	S07-33883	1.6	4.74	30	80	<5	3.70	3	22	239	77	5.44	2.26	20	2.10	963	27	0.17	111	880	50	10	<20	209	0.06	<10	224	<10	7	203
30	S07-33884	2.6	5.34	35	100	<5	3.60	2	23	449	65	5.35	2.03	20	1.74	1014	30	0.19	105	1120	58	15	<20	192	0.08	<10	252	<10	8	153
31	S07-33885	2.4	5.14	25	95	<5	2.66	1	20	490	70	5.22	2.14	20	1.49	888	28	0.17	79	1050	66	15	<20	172	0.09	<10	244	<10	7	112
32	S07-33886	2.0	5.25	20	120	<5	2.93	3	24	394	56	3.97	2.17	10	1.31	850	15	0.22	70	2240	354	5	<20	185	0.12	<10	221	<10	9	184
33	S07-33887	1.0	7.63	20	115	<5	3.28	1	21	287	91	4.28	1.89	10	1.51	829	25	0.91	58	2660	50	<5	<20	214	0.16	<10	194	<10	11	112
34	S07-33888	0.9	7.11	25	545	<5	3.95	<1	12	189	100	3.57	1.92	20	1.80	905	4	1.26	29	1080	30	<5	<20	211	0.13	<10	139	<10	9	80
35	S07-33889	0.8	5.86	135	180	<5	0.27	<1	8	22	31	3.43	4.41	10	0.30	165	3	0.31	15	530	20	40	<20	55	0.37	<10	79	<10	11	45
36	S07-33890	0.7	6.50	20	635	<5	3.77	<1	9	184	92	3.17	1.96	20	1.87	793	3	1.34	20	850	26	<5	<20	214	0.13	<10	125	<10	10	84
37	S07-33891	0.5	6.05	25	545	<5	2.36	<1	15	210	42	3.85	1.88	10	1.69	591	4	1.47	27	660	26	<5	<20	142	0.12	<10	130	<10	6	94
38	S07-33892	0.6	5.49	40	110	<5	1.80	1	19	366	48	5.11	1.98	10	1.52	516	4	1.54	33	600	24	5	<20	130	0.11	<10	134	<10	6	111
39	S07-33893	0.2	5.79	35	620	<5	2.50	<1	9	195	32	3.10	1.85	10	1.56	736	4	1.41	27	640	24	<5	<20	155	0.12	<10	139	<10	5	128
40	S07-33894	0.2	5.53	15	735	<5	2.30	<1	8	111	42	2.39	2.03	10	1.63	705	8	1.74	22	600	22	<5	<20	153	0.14	<10	163	<10	5	125
41	S07-33895	0.5	5.03	20	560	<5	2.03	<1	9	226	66	2.86	1.95	10	1.37	557	6	1.22	25	490	26	<5	<20	153	0.11	<10	146	<10	6	111

QC DATA:

Repeat:

1	S07-33855	0.2	5.09	40	730	<5	0.84	<1	12	90	24	1.60	2.33	10	0.99	1293	<1	0.81	43	350	22	<5	<20	80	0.11	<10	31	<10	5	40
10	S07-33864	0.7	5.06	155	580	<5	1.30	<1	23	604	89	5.46	1.79	10	0.77	1711	5	0.31	124	640	38	10	<20	101	0.09	<10	115	<10	5	126
19	S07-33873	0.9	4.07	95	410	<5	3.75	<1	34	821	62	4.81	1.63	10	3.95	1714	9	0.47	233	740	30	15	<20	292	0.06	<10	154	<10	6	128

Resplit:

1	S07-33855	<0.2	5.22	40	745	<5	0.78	<1	13	69	22	1.63	2.39	10	0.87	1233	<1	0.78	40	350	18	<5	<20	80	0.13	<10	36	<10	5	40
36	S07-33890	0.5	6.49	20	690	<5	3.61	<1	11	188	93	3.15	1.98	20	1.85	808	3	1.38	24	940	30	<5	<20	212	0.15	<10	127	<10	8	85


Standard:


Stsd3		0.5	5.70	25	1300	<5	2.58	1	15	59	36	4.26	1.45	40	1.32	2592	5	1.10	33	1710	60	<5	<20	240	0.34	<10	110	<10	29	207
Stsd3		0.5	5.84	20	1260	<5	2.43	<1	15	58	34	4.21	1.51	40	1.39	2510	5	1.17	33	1680	58	<5	<20	230	0.33	<10	115	<10	29	200

ICP: 4 ACID DIGEST/ICP-FINISH

AG: 4 ACID DIGEST/AA-FINISH

JJ/nw
df/tt2269s
XLS/07


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2271

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

11-Mar-08


Attention: Bob Singh

No. of samples received: 176
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-138
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-33896	0.25	0.007
2	S07-33897	0.60	0.017
3	S07-33898	0.69	0.020
4	S07-33899	0.08	0.002
5	S07-33900	0.10	0.003
6	S07-33901	<0.03	<0.001
7	S07-33902	0.04	0.001
8	S07-33903	0.06	0.002
9	S07-33904	<0.03	<0.001
10	S07-33905	<0.03	<0.001
11	S07-33906	0.29	0.008
12	S07-33907	0.23	0.007
13	S07-33908	1.45	0.042
14	S07-33909	1.11	0.032
15	S07-33910	0.04	0.001
16	S07-33911	0.49	0.014
17	S07-33912	<0.03	<0.001
18	S07-33913	0.69	0.020
19	S07-33914	0.32	0.009
20	S07-33915	0.12	0.004
21	S07-33916	0.10	0.003
22	S07-33917	0.05	0.001
23	S07-33918	<0.03	<0.001
24	S07-33919	<0.03	<0.001
25	S07-33920	<0.03	<0.001
26	S07-33921	2.05	0.060
27	S07-33922	<0.03	<0.001
28	S07-33923	<0.03	<0.001
29	S07-33924	<0.03	<0.001
30	S07-33925	<0.03	<0.001


* = 30g FA


Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
31	S07-33926	<0.03	<0.001
32	S07-33927	<0.03	<0.001
33	S07-33928	<0.03	<0.001
34	S07-33929	<0.03	<0.001
35	S07-33930	0.23	0.007
36	S07-33931	<0.03	<0.001
37	S07-33932	1.15	0.034
38	S07-33933	0.02	0.001
39	S07-33934	0.07	0.002
40	S07-33935	0.17	0.005
41	S07-33936	0.06	0.002
42	S07-33937	0.04	0.001
43	S07-33938	<0.03	<0.001
44	S07-33939	<0.03	<0.001
45	S07-33940	<0.03	<0.001
46	S07-33941	0.05	0.001
47	S07-33942	0.05	0.001
48	S07-33943	<0.03	<0.001
49	S07-33944	0.03	0.001
50	S07-33945	0.04	0.001
51	S07-33946	0.26	0.008
52	S07-33947	0.07	0.002
53	S07-33948	0.14	0.004
54	S07-33949	<0.03	<0.001
55	S07-33950	<0.03	<0.001
56	S07-33951	<0.03	<0.001
57	S07-33952	<0.03	<0.001
58	S07-33953	<0.03	<0.001
59	S07-33954	<0.03	<0.001
60	S07-33955	<0.03	<0.001
61	S07-33956	0.04	0.001
62	S07-33957	<0.03	<0.001
63	S07-33958	<0.03	<0.001
64	S07-33959	<0.03	<0.001
65	S07-33960	<0.03	<0.001
66	S07-33961	<0.03	<0.001
67	S07-33962	0.42	0.012
68	S07-33963	<0.03	<0.001
69	S07-33964	<0.03	<0.001
70	S07-33965	<0.03	<0.001
71	S07-33966	<0.03	<0.001
72	S07-33967	<0.03	<0.001
73	S07-33968	<0.03	<0.001
74	S07-33969	<0.03	<0.001
75	S07-33970	<0.03	<0.001


* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
76	S07-33971	<0.03	<0.001
77	S07-33972	<0.03	<0.001
78	S07-33973	<0.03	<0.001
79	S07-33974	<0.03	<0.001
80	S07-33975	<0.03	<0.001
81	S07-33976	<0.03	<0.001
82	S07-33977	<0.03	<0.001
83	S07-33978	<0.03	<0.001
84	S07-33979	<0.03	<0.001
85	S07-33980	0.03	0.001
86	S07-33981	0.07	0.002
87	S07-33982	0.15	0.004
88	S07-33983	0.04	0.001
89	S07-33984	<0.03	<0.001
90	S07-33985	<0.03	<0.001
91	S07-33986	<0.03	<0.001
92	S07-33987	<0.03	<0.001
93	S07-33988	<0.03	<0.001
94	S07-33989	<0.03	<0.001
95	S07-33990	<0.03	<0.001
96	S07-33991	<0.03	<0.001
97	S07-33992	<0.03	<0.001
98	S07-33993	<0.03	<0.001
99	S07-33994	0.21	0.006
100	S07-33995	<0.03	<0.001
101	S07-33996	<0.03	<0.001
102	S07-33997	2.06	0.060
103	S07-33998	<0.03	<0.001
104	S07-33999	<0.03	<0.001
105	S07-34000	<0.03	<0.001
106	S07-34001	0.04	0.001
107	S07-34002	<0.03	<0.001
108	S07-34003	<0.03	<0.001
109	S07-34004	<0.03	<0.001
110	S07-34005	0.04	0.001
111	S07-34006	<0.03	<0.001
112	S07-34007	0.44	0.013
113	S07-34008	<0.03	<0.001
114	S07-34009	<0.03	<0.001
115	S07-34010	<0.03	<0.001
116	S07-34011	<0.03	<0.001
117	S07-34012	<0.03	<0.001
118	S07-34013	<0.03	<0.001
119	S07-34014	<0.03	<0.001
120	S07-34015	<0.03	<0.001

* = 30g FA


Eco Tech LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
121	S07-34016	<0.03	<0.001
122	S07-34017	<0.03	<0.001
123	S07-34018	0.05	0.002
124	S07-34019	<0.03	<0.001
125	S07-34020	<0.03	<0.001
126	S07-34021	<0.03	<0.001
127	S07-34022	0.03	0.001
128	S07-34023	<0.03	<0.001
129	S07-34024	<0.03	<0.001
130	S07-34025	<0.03	<0.001
131	S07-34026	<0.03	<0.001
132	S07-34027	<0.03	<0.001
133	S07-34028	<0.03	<0.001
134	S07-34029	<0.03	<0.001
135	S07-34030	<0.03	<0.001
136	S07-34031	<0.03	<0.001
137	S07-34032	<0.03	<0.001
138	S07-34033	<0.03	<0.001
139	S07-34034	<0.03	<0.001
140	S07-34035	<0.03	<0.001
141	S07-34036	<0.03	<0.001
142	S07-34037	<0.03	<0.001
143	S07-34038	<0.03	<0.001
144	S07-34039	<0.03	<0.001
145	S07-34040	0.04	0.001
146	S07-34041	<0.03	<0.001
147	S07-34042	0.15	0.004
148	S07-34043	<0.03	<0.001
149	S07-34044	<0.03	<0.001
150	S07-34045	<0.03	<0.001
151	S07-34046	<0.03	<0.001
152	S07-34047	<0.03	<0.001
153	S07-34048	<0.03	<0.001
154	S07-34049	<0.03	<0.001
155	S07-34050	<0.03	<0.001
156	S07-34051	<0.03	<0.001
157	S07-34052	<0.03	<0.001
158	S07-34053	2.03	0.059
159	S07-34054	<0.03	<0.001
160	S07-34055	<0.03	<0.001
161	S07-34056	<0.03	<0.001
162	S07-34057	<0.03	<0.001
163	S07-34058	<0.03	<0.001
164	S07-34059	<0.03	<0.001
165	S07-34060	<0.03	<0.001

* = 30g FA



 ECO TECH LABORATORY LTD.

 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
166	S07-34061	<0.03	<0.001
167	S07-34062	<0.03	<0.001
168	S07-34063	<0.03	<0.001
169	S07-34064	<0.03	<0.001
170	S07-34065	<0.03	<0.001
171	S07-34066	<0.03	<0.001
172	S07-34067	0.04	0.001
173	S07-34068	<0.03	<0.001
174	S07-34069	<0.03	<0.001
175	S07-34070	<0.03	<0.001
176	S07-34071	<0.03	<0.001

QC DATA:**Resplit:**

1	S07-33896	0.20	0.006
36	S07-33931	<0.03	<0.001
71	S07-33966	<0.03	<0.001
106	S07-34001	<0.03	<0.001
141	S07-34036	<0.03	<0.001
176	S07-34071	<0.03	<0.001

Standard:

OXI54	1.89	0.055
OXI54	1.87	0.055
OXI54	1.84	0.054
OXI54	1.88	0.055
OXI54	1.86	0.054
OXI54	1.89	0.055
OXI54	1.88	0.055
OXI54	1.88	0.055
OXI54	1.86	0.054
OXI54	1.86	0.054
OXI54	1.84	0.054
OXI54	1.90	0.055
OXI54	1.90	0.055
OXI54	1.86	0.054
OXI54	1.85	0.054

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw

KLS/07



ECO TECH LABORATORY LTD.

Jutta Bealouse

B.C. Certified Assayer

ECO TECH LABO. .ORY LTD.

10041 Dallas Drive

KAMLOOPS, B.C.

V2C 6T4

Phone: 250-573-5700

Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS . . 2007-2271

Skygold Ventures

615 - 800 W. Pender Street

Vancouver, BC

V6B 2V6

No. of samples received: 176

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-138

Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-33896	0.6	5.88	20	475	<5	2.79	2	10	115	77	2.45	1.99	20	1.50	716	9	1.11	34	660	32	<5	<20	192	0.11	<10	219	<10	7	162
2	S07-33897	1.4	5.95	25	105	<5	1.96	2	25	156	127	5.02	2.38	10	1.49	633	18	0.77	62	690	34	<5	<20	145	0.08	<10	284	<10	5	226
3	S07-33898	0.6	5.93	20	250	<5	1.71	2	14	104	76	3.35	2.10	20	1.28	431	18	0.85	42	1090	40	<5	<20	117	0.09	<10	179	<10	7	194
4	S07-33899	0.6	7.67	10	1410	<5	2.15	<1	13	72	64	4.16	2.36	20	2.34	576	<1	1.58	20	860	50	<5	<20	166	0.10	<10	144	<10	7	129
5	S07-33900	0.4	6.74	15	980	<5	2.74	<1	13	78	40	3.44	2.07	20	2.05	804	1	1.95	17	660	38	<5	<20	214	0.09	<10	136	<10	7	80
6	S07-33901	0.4	7.13	20	1200	<5	2.13	<1	13	74	45	4.00	1.96	20	2.18	757	1	2.47	20	750	36	<5	<20	191	0.10	<10	127	<10	7	93
7	S07-33902	0.4	7.68	20	395	<5	1.79	<1	16	90	40	4.34	2.02	10	2.09	672	2	2.56	24	740	40	<5	<20	173	0.10	<10	132	<10	6	113
8	S07-33903	0.6	7.26	25	365	<5	3.03	<1	10	65	40	2.94	2.07	20	1.58	939	1	2.60	18	620	32	<5	<20	218	0.10	<10	143	<10	6	51
9	S07-33904	0.4	6.20	15	1140	<5	1.72	<1	9	86	57	2.40	1.90	10	1.33	562	2	1.95	17	540	26	<5	<20	149	0.11	<10	114	<10	6	75
10	S07-33905	0.4	6.21	<5	1530	<5	1.76	<1	5	80	31	2.43	2.40	20	1.49	522	2	1.11	14	520	24	<5	<20	138	0.10	<10	88	<10	6	77
11	S07-33906	0.6	5.91	15	535	<5	2.15	<1	11	101	68	3.06	2.09	20	1.36	563	5	1.00	29	650	56	<5	<20	136	0.10	<10	161	<10	6	106
12	S07-33907	0.8	6.51	15	250	<5	3.44	<1	14	92	156	3.64	2.19	20	1.64	783	<1	1.22	35	810	30	<5	<20	188	0.12	<10	153	<10	6	101
13	S07-33908	1.2	6.01	30	145	<5	3.35	<1	13	93	84	3.77	2.36	20	1.40	662	54	0.59	55	860	26	<5	<20	158	0.10	<10	281	<10	5	49
14	S07-33909	0.8	8.40	30	960	<5	6.02	<1	23	59	123	5.14	2.46	<10	3.19	1198	<1	1.38	19	840	44	<5	<20	389	0.12	<10	206	<10	9	124
15	S07-33910	1.0	6.35	30	150	<5	4.30	2	18	108	100	5.03	2.54	10	1.83	793	33	0.93	49	1110	32	<5	<20	202	0.10	<10	442	<10	6	203
16	S07-33911	0.8	5.94	20	175	<5	3.40	4	15	125	142	3.77	2.07	20	1.40	701	46	0.89	64	1350	28	<5	<20	161	0.12	<10	603	<10	6	406
17	S07-33912	<0.2	0.06	<5	25	<5	>10	<1	<1	<1	1	0.52	0.03	<10	>10	185	<1	0.03	2	200	<2	<5	<20	55	<0.01	<10	3	<10	<1	12
18	S07-33913	1.2	5.56	20	185	<5	2.79	3	13	119	75	3.24	2.05	20	1.11	438	23	0.61	51	1760	24	<5	<20	130	0.10	<10	492	<10	7	292
19	S07-33914	1.6	6.48	20	135	<5	4.15	1	18	82	102	5.05	1.98	20	1.62	683	14	1.53	37	860	38	<5	<20	189	0.11	<10	200	<10	7	157
20	S07-33915	0.8	7.83	20	230	<5	5.12	2	18	90	113	4.60	2.00	20	2.01	707	16	1.40	28	940	38	<5	<20	244	0.13	<10	317	<10	9	236
21	S07-33916	0.6	5.85	15	360	<5	4.60	3	8	103	76	3.40	2.00	20	1.60	844	50	0.69	41	880	24	<5	<20	193	0.09	<10	332	<10	7	308
22	S07-33917	0.6	7.28	25	275	<5	4.82	<1	14	76	52	4.45	2.10	20	1.65	1027	2	1.48	16	1150	28	<5	<20	295	0.13	<10	113	<10	9	76
23	S07-33918	0.4	7.93	15	525	<5	4.88	<1	16	82	77	4.67	1.54	20	1.79	1265	<1	3.04	22	990	32	<5	<20	443	0.14	<10	143	<10	6	82
24	S07-33919	0.4	8.03	10	330	<5	4.68	<1	18	72	69	4.80	1.07	10	1.93	1427	<1	3.23	25	750	28	<5	<20	462	0.14	<10	167	<10	4	84
25	S07-33920	0.4	7.69	15	495	<5	4.40	<1	16	75	60	4.39	1.44	10	1.94	1285	<1	2.75	23	650	28	<5	<20	448	0.14	<10	143	<10	5	64

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
26	S07-33921	5.0	4.71	105	340	<5	0.48	1	11	36	580	4.92	2.39	10	1.77	380	7	0.24	23	510	98	45	<20	73	0.27	<10	52	<10	10	660
27	S07-33922	0.4	7.97	15	510	<5	4.78	<1	18	82	62	4.49	1.50	10	2.16	1331	<1	2.49	28	690	30	<5	<20	536	0.14	<10	162	<10	4	73
28	S07-33923	0.6	6.79	15	510	<5	4.41	<1	18	92	75	4.16	1.83	10	1.71	948	3	2.08	24	710	28	<5	<20	328	0.12	<10	134	<10	6	68
29	S07-33924	0.6	8.39	10	760	<5	5.02	<1	15	76	73	4.06	2.10	10	1.72	916	6	2.43	20	870	34	<5	<20	417	0.15	<10	172	<10	6	67
30	S07-33925	0.4	8.05	10	465	<5	4.08	<1	14	72	67	4.46	1.28	10	1.60	978	<1	2.60	19	840	30	<5	<20	505	0.17	<10	134	<10	4	58
31	S07-33926	0.2	8.98	10	600	<5	4.56	<1	19	50	53	5.35	1.47	<10	2.30	1213	<1	2.78	23	830	30	<5	<20	522	0.15	<10	206	<10	3	65
32	S07-33927	0.2	9.15	10	475	<5	5.47	<1	18	38	72	4.91	1.20	<10	2.16	1307	<1	3.25	18	960	30	<5	<20	525	0.16	<10	198	<10	5	60
33	S07-33928	0.4	7.53	10	400	<5	4.47	<1	15	32	60	4.29	1.19	<10	1.67	1081	<1	2.60	15	730	26	<5	<20	486	0.15	<10	163	<10	3	50
34	S07-33929	0.4	7.81	10	530	<5	5.80	<1	13	68	58	3.89	1.76	10	1.52	1181	<1	2.60	18	1050	30	<5	<20	478	0.16	<10	122	<10	6	50
35	S07-33930	0.4	8.72	10	905	<5	6.28	<1	16	59	85	4.46	2.09	10	2.01	1298	<1	3.21	18	980	34	<5	<20	570	0.19	<10	169	<10	6	50
36	S07-33931	0.8	8.07	10	515	<5	4.99	<1	16	59	127	4.95	1.98	10	1.81	1048	<1	3.28	17	1270	30	<5	<20	385	0.19	<10	185	<10	7	58
37	S07-33932	1.0	6.26	10	330	<5	5.75	<1	18	99	319	5.97	1.71	20	1.86	1088	2	2.38	12	2190	28	<5	<20	474	0.22	<10	189	<10	12	50
38	S07-33933	1.0	7.57	5	345	<5	4.95	<1	20	36	259	6.57	1.73	20	1.87	1351	<1	2.89	12	1940	30	<5	<20	341	0.29	<10	224	<10	11	56
39	S07-33934	0.8	7.47	10	405	<5	4.71	<1	19	43	168	6.10	2.03	20	1.92	1284	<1	2.57	13	1830	34	<5	<20	308	0.26	<10	209	<10	12	68
40	S07-33935	0.6	7.61	20	845	<5	4.27	<1	17	93	54	4.13	2.46	10	1.82	1061	<1	0.70	36	880	32	<5	<20	253	0.17	<10	141	<10	5	81
41	S07-33936	0.4	5.92	80	615	<5	2.95	<1	15	110	106	3.04	1.62	20	1.78	1313	6	0.18	100	630	32	<5	<20	180	0.18	<10	129	<10	9	161
42	S07-33937	0.4	6.15	55	675	<5	3.16	<1	14	91	82	3.61	1.74	20	1.97	1526	2	0.34	76	680	30	<5	<20	213	0.16	<10	112	<10	8	120
43	S07-33938	<0.2	0.11	<5	25	<5	>10	<1	<1	1	2	0.50	0.06	<10	>10	179	<1	0.09	2	160	<2	<5	<20	53	<0.01	<10	<1	<10	<1	15
44	S07-33939	0.4	7.11	15	955	<5	3.00	<1	21	66	66	5.18	1.25	<10	2.53	1087	<1	3.75	29	1050	24	<5	<20	294	0.19	<10	192	<10	4	57
45	S07-33940	0.4	6.72	10	470	<5	2.91	<1	19	83	73	4.95	0.72	<10	2.39	1050	<1	3.75	30	1060	22	<5	<20	330	0.18	<10	176	<10	4	58
46	S07-33941	0.4	7.59	20	1145	<5	4.07	<1	20	87	77	4.72	1.49	10	2.52	1651	5	2.45	40	860	32	<5	<20	418	0.16	<10	207	<10	5	107
47	S07-33942	1.0	6.05	55	270	<5	1.88	<1	17	106	92	3.28	1.68	20	1.56	2775	<1	0.60	94	440	40	<5	<20	203	0.15	<10	85	<10	5	96
48	S07-33943	1.7	4.74	60	805	<5	1.71	<1	18	125	156	3.20	1.44	10	1.65	3645	1	0.67	166	500	40	<5	<20	202	0.12	<10	81	<10	4	162
49	S07-33944	1.0	4.84	55	885	<5	1.21	<1	11	98	95	2.87	1.59	20	1.74	2345	<1	0.43	119	420	30	<5	<20	138	0.13	<10	77	<10	4	121
50	S07-33945	1.2	5.15	105	1010	<5	1.88	1	16	104	223	3.42	1.83	20	1.81	2436	1	0.30	283	400	36	<5	<20	192	0.14	<10	87	<10	5	234
51	S07-33946	1.4	5.36	100	160	<5	2.35	3	16	141	150	3.41	1.47	20	1.38	2324	29	0.15	196	500	34	<5	<20	206	0.17	<10	361	<10	7	385
52	S07-33947	1.4	4.90	75	120	<5	2.46	5	22	159	92	4.17	2.00	20	1.39	2062	25	0.14	171	550	36	5	<20	218	0.12	<10	346	<10	7	486
53	S07-33948	1.0	4.33	45	185	<5	2.26	2	18	147	88	3.48	1.48	10	1.37	1846	8	0.10	127	350	28	<5	<20	217	0.10	<10	147	<10	4	177
54	S07-33949	0.3	4.24	40	1330	<5	1.76	<1	13	181	72	2.39	1.68	20	1.25	1307	<1	0.11	90	300	20	<5	<20	164	0.11	<10	69	<10	4	98
55	S07-33950	0.4	4.74	25	1700	<5	1.32	<1	8	115	42	2.12	1.87	20	1.35	1149	<1	0.19	45	350	24	<5	<20	154	0.12	<10	66	<10	4	78
56	S07-33951	0.8	4.29	40	1525	<5	0.89	<1	10	134	91	2.12	1.80	20	1.07	625	<1	0.15	64	280	24	<5	<20	94	0.12	<10	63	<10	3	114
57	S07-33952	0.4	4.28	45	1405	<5	1.05	<1	9	146	79	2.27	1.74	20	1.10	678	<1	0.15	70	280	24	<5	<20	96	0.12	<10	61	<10	4	126
58	S07-33953	0.6	5.72	30	2195	<5	1.86	<1	9	93	37	2.23	1.75	20	1.47	941	<1	0.23	51	350	26	<5	<20	173	0.13	<10	65	<10	5	59
59	S07-33954	0.2	6.55	20	2560	<5	2.08	<1	7	97	46	2.57	1.56	20	1.71	981	<1	0.29	38	390	24	<5	<20	182	0.14	<10	72	<10	6	86
60	S07-33955	0.2	4.57	30	1370	<5	1.82	1	10	140	38	2.63	1.72	10	1.44	767	2	0.18	55	330	24	<5	<20	158	0.12	<10	110	<10	4	161
61	S07-33956	0.4	5.69	30	530	<5	1.86	2	15	118	139	3.48	1.60	20	1.60	771	5	0.23	45	660	26	<5	<20	159	0.15	<10	197	<10	5	234
62	S07-33957	0.4	7.08	15	3160	<5	3.26	<1	16	73	79	4.45	1.64	20	2.62	1105	<1	1.77	24	890	26	<5	<20	304	0.18	<10	164	<10	6	75
63	S07-33958	0.4	8.49	20	2190	<5	2.35	<1	20	62	82	4.82	1.71	10	2.31	1055	<1	2.87	25	950	30	<5	<20	323	0.15	<10	169	<10	5	78
64	S07-33959	0.6	8.55	15	2420	<5	2.47	<1	20	74	88	5.45	1.31	10	2.74	1316	<1	3.20	25	1100	30	<5	<20	366	0.17	<10	184	<10	5	75
65	S07-33960	0.4	8.76	20	910	<5	3.78	<1	24	64	89	5.86	1.38	10	2.88	1627	<1	3.51	29	1120	30	<5	<20	491	0.19	<10	197	<10	6	58


Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn	
66	S07-33961	0.4	8.03	10	2090	<5	3.72	<1	18	65	98	5.47	1.12	10	3.07	1880	<1	3.77	24	1150	26	<5	<20	499	0.19	<10	177	<10	6	59
67	S07-33962	0.9	5.88	125	445	<5	0.27	<1	7	25	30	3.11	4.62	10	0.33	162	3	0.14	15	490	18	40	<20	56	0.38	<10	68	<10	11	48
68	S07-33963	0.6	7.89	15	2700	<5	4.62	<1	20	58	92	5.46	1.49	10	3.05	1983	<1	3.10	24	1110	30	<5	<20	606	0.19	<10	191	<10	7	53
69	S07-33964	0.4	8.13	10	2965	<5	2.72	<1	23	66	85	5.85	1.48	<10	3.11	1695	<1	3.26	28	1040	28	<5	<20	450	0.18	<10	200	<10	5	70
70	S07-33965	0.6	8.65	15	4010	<5	3.21	<1	25	70	93	6.09	2.05	10	3.33	1784	<1	2.90	32	1130	30	<5	<20	473	0.21	<10	240	<10	5	65
71	S07-33966	0.6	8.17	20	2870	<5	3.33	<1	25	78	77	5.61	1.74	10	2.93	1631	<1	3.30	32	1030	32	<5	<20	474	0.20	<10	196	<10	6	58
72	S07-33967	0.4	7.12	10	2000	<5	3.93	<1	10	66	76	3.92	1.64	20	2.00	1205	<1	3.15	15	980	28	<5	<20	525	0.14	<10	110	<10	9	43
73	S07-33968	0.4	7.36	15	3260	<5	2.40	<1	21	81	73	6.19	2.00	10	3.41	1652	<1	2.58	31	1040	28	<5	<20	338	0.20	<10	199	<10	6	62
74	S07-33969	0.4	6.95	20	2220	<5	3.25	<1	16	70	59	4.55	1.69	20	2.52	1442	<1	2.58	24	1020	32	<5	<20	421	0.18	<10	129	<10	7	58
75	S07-33970	0.6	8.21	15	2320	<5	2.11	<1	15	73	58	4.44	1.31	20	1.94	1113	<1	3.65	18	860	32	<5	<20	336	0.19	<10	135	<10	6	76
76	S07-33971	0.4	6.39	5	2455	<5	1.00	<1	5	34	38	2.84	1.07	10	1.20	587	<1	4.22	8	690	26	<5	<20	240	0.17	<10	70	<10	6	46
77	S07-33972	0.6	6.91	35	890	<5	4.69	<1	20	188	75	4.48	1.25	10	2.26	1385	<1	3.25	56	880	28	<5	<20	518	0.16	<10	144	<10	7	53
78	S07-33973	0.6	7.41	20	1830	<5	4.07	<1	17	155	85	4.79	1.73	10	2.51	1304	<1	2.80	40	990	32	<5	<20	506	0.17	<10	177	<10	7	66
79	S07-33974	0.4	6.16	10	760	<5	3.48	<1	8	56	27	2.96	0.75	10	1.54	980	<1	4.04	11	730	24	<5	<20	383	0.16	<10	69	<10	6	35
80	S07-33975	0.6	6.90	10	1110	<5	2.38	<1	11	61	49	3.87	1.08	10	1.65	1098	<1	3.55	15	900	26	<5	<20	346	0.20	<10	106	<10	5	53
81	S07-33976	0.4	5.49	<5	925	<5	1.31	<1	5	56	25	2.31	0.80	<10	0.98	714	<1	4.32	9	460	20	<5	<20	294	0.20	<10	47	<10	4	41
82	S07-33977	0.4	6.43	10	780	<5	1.55	<1	7	63	24	2.50	0.70	10	1.10	883	<1	4.55	9	490	24	<5	<20	321	0.19	<10	43	<10	5	43
83	S07-33978	0.4	6.54	15	900	<5	2.41	<1	13	83	60	4.09	1.00	20	1.58	1055	<1	4.03	16	1060	26	<5	<20	379	0.23	<10	110	<10	6	60
84	S07-33979	0.4	8.09	20	1235	<5	3.73	<1	19	89	69	4.88	1.89	20	2.80	1732	<1	3.33	26	1070	28	<5	<20	463	0.24	<10	189	<10	6	77
85	S07-33980	0.6	3.60	15	350	<5	1.95	<1	8	143	16	2.33	0.62	<10	1.08	614	<1	1.42	14	440	16	<5	<20	226	0.12	<10	64	<10	4	34
86	S07-33981	0.4	7.49	20	1570	<5	3.46	<1	18	99	61	4.63	2.52	10	2.45	1230	<1	1.69	25	910	32	<5	<20	380	0.20	<10	153	<10	6	98
87	S07-33982	0.6	5.19	45	395	<5	3.04	<1	12	149	67	3.46	1.92	20	1.60	1271	4	0.18	70	470	32	<5	<20	273	0.14	<10	126	<10	6	115
88	S07-33983	0.8	4.92	45	1025	<5	4.09	1	10	270	67	2.90	1.91	20	1.85	985	7	0.16	72	630	52	<5	<20	346	0.13	<10	201	<10	7	158
89	S07-33984	0.6	8.78	20	925	<5	4.49	<1	21	74	81	5.49	1.90	10	3.18	1316	<1	3.70	30	1260	38	<5	<20	454	0.18	<10	204	<10	6	87
90	S07-33985	0.2	8.16	20	710	<5	3.78	<1	18	72	55	4.60	1.66	<10	2.83	1109	<1	3.65	24	1010	32	<5	<20	396	0.18	<10	191	<10	5	70
91	S07-33986	0.4	8.34	15	530	<5	3.25	<1	22	85	66	5.70	1.03	<10	3.60	1504	<1	4.16	33	1120	30	<5	<20	380	0.19	<10	208	<10	5	51
92	S07-33987	0.4	7.77	15	610	<5	5.56	<1	20	105	77	5.32	1.36	10	3.39	1726	<1	3.32	33	1110	30	<5	<20	515	0.16	<10	215	<10	7	45
93	S07-33988	<0.2	0.07	<5	15	5	>10	<1	<1	1	2	0.54	0.03	<10	>10	185	<1	0.04	2	160	<2	<5	<20	56	<0.01	<10	1	<10	<1	12
94	S07-33989	0.4	8.28	20	580	<5	2.78	<1	21	80	56	5.46	1.21	10	3.23	1174	<1	3.98	31	990	32	<5	<20	358	0.22	<10	208	<10	6	79
95	S07-33990	0.6	8.69	20	1020	<5	3.49	<1	25	85	67	5.96	1.93	10	3.37	1500	<1	3.41	34	1030	32	<5	<20	389	0.22	<10	213	<10	6	90
96	S07-33991	0.6	8.71	20	1035	<5	2.33	<1	25	79	92	5.67	1.59	10	3.36	1320	<1	3.52	34	1040	28	<5	<20	331	0.27	<10	226	<10	5	88
97	S07-33992	0.8	8.54	20	985	<5	2.52	<1	24	75	89	5.79	1.49	10	3.20	1299	<1	3.63	30	1020	34	5	<20	352	0.25	<10	213	<10	4	72
98	S07-33993	<0.2	7.90	10	1120	<5	2.93	<1	21	70	80	5.49	1.81	10	3.20	1213	<1	3.36	26	920	30	<5	<20	372	0.18	<10	205	<10	6	69
99	S07-33994	0.8	5.43	25	125	<5	3.54	<1	12	95	72	4.04	2.21	20	1.71	1024	4	0.52	64	650	36	<5	<20	317	0.13	<10	118	<10	7	101
100	S07-33995	0.4	6.52	15	1900	<5	1.92	<1	13	89	53	3.63	2.58	20	2.11	759	<1	1.39	33	710	30	<5	<20	237	0.17	<10	167	<10	5	89
101	S07-33996	0.8	8.01	15	965	<5	3.63	<1	23	66	78	5.52	1.36	10	2.99	1457	<1	3.22	30	1030	30	<5	<20	421	0.20	<10	214	<10	5	73
102	S07-33997	5.0	4.27	120	325	<5	0.47	1	10	36	595	4.96	2.62	10	1.71	345	6	0.23	21	460	92	45	<20	74	0.26	<10	52	<10	10	668
103	S07-33998	0.4	6.66	20	1150	<5	4.17	<1	11	78	51	4.16	1.69	20	2.42	1421	<1	1.82	29	750	26	<5	<20	408	0.16	<10	154	<10	7	99
104	S07-33999	0.4	8.39	20	1095	<5	3.69	<1	25	105	91	5.56	1.60	10	3.57	1238	<1	3.03	38	1000	30	<5	<20	406	0.22	<10	229	<10	7	70
105	S07-34000	0.6	7.78	35	885	<5	5.16	<1	29	225	86	6.50	1.22	10	4.06	1252	<1	2.47	78	1150	32	<5	<20	542	0.19	<10	231	<10	8	84


Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K ₂ O	Li	mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn	
106	S07-34001	0.8	8.15	15	1150	<5	3.65	<1	25	55	117	5.52	0.97	10	2.41	1081	<1	3.54	26	1120	36	<5	<20	447	0.25	<10	213	<10	7	70
107	S07-34002	0.6	8.17	15	635	<5	4.85	<1	19	73	66	5.85	0.94	<10	2.85	1224	<1	3.81	28	1110	32	<5	<20	584	0.24	<10	210	<10	7	61
108	S07-34003	0.6	8.72	10	655	<5	3.96	<1	22	59	102	5.79	0.96	10	2.60	1038	<1	3.78	30	1110	36	<5	<20	499	0.25	<10	205	<10	8	72
109	S07-34004	0.6	9.27	10	905	<5	5.01	<1	23	80	89	6.42	2.11	10	2.89	1237	<1	3.40	30	1310	36	<5	<20	548	0.23	<10	236	<10	8	69
110	S07-34005	0.4	8.19	10	960	<5	3.96	<1	23	53	93	6.07	1.33	<10	2.72	1165	<1	3.53	23	940	28	<5	<20	424	0.23	<10	226	<10	7	65
111	S07-34006	0.6	8.38	5	425	<5	4.18	<1	23	66	89	6.18	0.73	<10	2.78	1186	<1	4.10	26	910	30	<5	<20	453	0.26	<10	229	<10	7	75
112	S07-34007	0.9	5.73	105	375	<5	0.28	<1	8	25	32	3.17	4.42	10	0.32	179	4	0.11	16	530	20	45	<20	60	0.40	<10	70	<10	11	51
113	S07-34008	0.6	8.56	10	920	<5	3.47	<1	23	73	79	5.80	1.37	10	2.48	1011	<1	4.15	32	970	32	<5	<20	418	0.22	<10	231	<10	6	75
114	S07-34009	0.6	8.12	10	1290	<5	3.88	<1	20	66	126	5.27	1.99	10	2.86	1130	<1	3.41	22	920	26	<5	<20	501	0.21	<10	269	<10	6	47
115	S07-34010	0.8	8.25	10	1190	<5	4.03	<1	22	64	84	5.59	1.50	10	2.66	1180	<1	4.00	27	1120	30	<5	<20	511	0.20	<10	221	<10	7	75
116	S07-34011	0.4	8.11	5	1355	<5	3.56	<1	22	44	104	5.31	1.37	10	2.26	1020	<1	4.36	23	950	28	<5	<20	490	0.19	<10	207	<10	6	73
117	S07-34012	0.4	7.82	5	580	<5	3.14	<1	20	42	96	5.16	0.92	<10	1.90	886	<1	4.88	15	940	30	<5	<20	447	0.21	<10	180	<10	5	73
118	S07-34013	0.4	8.07	5	565	<5	3.50	<1	17	46	93	5.20	0.92	<10	1.93	919	<1	4.76	15	950	32	<5	<20	457	0.21	<10	174	<10	5	62
119	S07-34014	0.6	8.70	10	780	<5	3.54	<1	18	45	86	5.67	1.07	10	2.26	1049	<1	4.41	17	1300	32	<5	<20	513	0.23	<10	180	<10	7	74
120	S07-34015	0.6	8.64	10	1060	<5	4.81	<1	25	62	83	6.51	1.69	10	2.96	1361	<1	3.65	32	1250	32	<5	<20	584	0.23	<10	246	<10	7	87
121	S07-34016	0.8	9.09	10	755	<5	4.41	<1	22	42	140	6.95	1.44	10	2.93	1407	<1	4.40	21	1970	36	<5	<20	574	0.30	<10	281	<10	8	77
122	S07-34017	0.8	8.81	5	730	<5	4.07	<1	23	63	118	6.75	1.27	10	3.13	1387	<1	3.91	27	1380	34	<5	<20	551	0.26	<10	273	<10	7	86
123	S07-34018	0.6	8.31	15	985	<5	5.63	<1	27	119	101	6.40	1.36	<10	2.94	1469	<1	4.04	50	1190	36	<5	<20	640	0.21	<10	236	<10	6	91
124	S07-34019	0.4	8.66	10	1310	<5	4.87	<1	25	64	85	5.80	1.29	10	2.74	1314	<1	4.00	29	1530	32	<5	<20	585	0.23	<10	203	<10	7	65
125	S07-34020	0.4	8.50	10	755	<5	4.40	<1	22	55	89	5.75	1.03	10	2.64	1305	<1	4.34	25	1100	28	<5	<20	600	0.29	<10	242	<10	6	67
126	S07-34021	0.6	8.13	5	855	<5	4.07	<1	19	55	91	5.91	0.99	10	2.42	1202	<1	4.44	22	1380	26	<5	<20	585	0.25	<10	235	<10	5	69
127	S07-34022	0.6	7.73	5	415	<5	4.07	<1	20	81	152	5.43	1.00	20	2.06	934	3	4.79	35	1480	30	<5	<20	519	0.22	<10	224	<10	8	70
128	S07-34023	0.6	7.97	10	425	<5	4.84	<1	20	86	113	5.91	1.16	20	2.48	1026	3	3.77	39	1500	38	<5	<20	472	0.27	<10	226	<10	9	70
129	S07-34024	0.4	7.63	15	1290	<5	4.47	<1	29	178	48	6.33	1.18	10	3.75	1283	<1	2.96	72	1130	34	<5	<20	434	0.15	<10	250	<10	7	99
130	S07-34025	0.4	7.52	10	765	<5	4.43	<1	30	177	117	6.32	0.72	10	3.87	1160	<1	3.47	73	1190	32	<5	<20	392	0.12	<10	222	<10	7	71
131	S07-34026	0.6	8.74	10	1875	<5	3.32	<1	26	164	117	6.29	1.32	10	3.57	1148	<1	3.31	58	1220	32	<5	<20	331	0.16	<10	218	<10	5	77
132	S07-34027	<0.2	0.12	<5	20	<5	>10	<1	1	2	2	0.52	0.05	<10	>10	192	<1	0.03	2	240	2	<5	<20	65	<0.01	<10	2	<10	<1	23
133	S07-34028	0.8	8.88	5	2895	<5	2.04	<1	20	72	145	5.51	1.96	10	3.27	1046	<1	2.75	28	1080	28	<5	<20	259	0.18	<10	228	<10	5	68
134	S07-34029	0.6	9.43	10	2505	<5	2.50	<1	26	87	66	6.48	1.76	10	3.83	1468	<1	3.16	35	1280	32	<5	<20	286	0.17	<10	229	<10	5	87
135	S07-34030	0.4	8.35	10	1430	<5	3.56	<1	21	104	72	5.05	1.32	10	3.27	1409	<1	3.56	31	1090	30	<5	<20	343	0.20	<10	197	<10	6	80
136	S07-34031	0.6	7.89	15	800	<5	6.17	<1	21	92	65	5.86	1.62	<10	3.63	1585	<1	3.45	34	870	42	<5	<20	588	0.16	<10	154	<10	8	96
137	S07-34032	0.6	8.27	20	645	<5	3.85	<1	18	76	58	4.96	1.19	<10	3.27	1359	<1	2.80	27	1020	32	<5	<20	478	0.19	<10	207	<10	8	71
138	S07-34033	0.8	8.21	35	1810	<5	3.70	<1	21	80	67	5.12	1.88	10	2.84	1143	<1	1.33	44	980	36	<5	<20	408	0.20	<10	186	<10	10	93
139	S07-34034	0.6	7.68	15	3800	<5	2.47	<1	15	84	94	4.70	2.42	10	2.53	923	2	1.01	34	950	34	<5	<20	258	0.16	<10	206	<10	6	112
140	S07-34035	0.4	7.79	15	965	<5	5.05	<1	25	81	83	5.88	1.60	10	3.26	1859	<1	2.60	34	1130	30	<5	<20	513	0.20	<10	199	<10	6	61
141	S07-34036	0.6	7.01	15	2840	<5	3.57	<1	16	98	79	4.39	1.88	10	2.42	1231	<1	1.48	42	810	34	<5	<20	361	0.16	<10	159	<10	7	72
142	S07-34037	0.6	8.53	15	1330	<5	3.10	<1	22	84	71	5.00	1.18	10	2.84	1219	<1	3.97	38	1070	36	<5	<20	371	0.19	<10	193	<10	6	92
143	S07-34038	0.4	8.39	10	615	<5	2.83	<1	26	90	92	5.89	0.81	10	3.09	1434	<1	3.79	36	1040	34	<5	<20	335	0.22	<10	213	<10	6	83
144	S07-34039	0.8	7.84	10	1385	<5	4.11	<1	21	81	84	5.56	1.65	10	3.03	1437	<1	2.18	30	1030	34	<5	<20	395	0.17	<10	190	<10	7	106
145	S07-34040	0.4	7.65	15	1460	<5	5.84	<1	21	96	96	5.10	1.89	10	2.72	2168	<1	1.64	43	970	34	<5	<20	456	0.16	<10	160	<10	6	87

Et #.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
115	S07-34010	0.6	8.65	5	1180	<5	4.35	<1	22	63	85	5.84	1.54	10	2.65	1218	<1	3.93	28	1160	32	<5	<20	507	0.21	<10	224	<10	7	70	
124	S07-34019	0.6	8.46	10	1300	<5	4.60	<1	24	62	82	5.66	1.30	10	2.73	1271	<1	4.07	28	1480	28	<5	<20	578	0.23	<10	205	<10	8	62	
141	S07-34036	0.6	7.22	20	2830	<5	3.78	<1	16	98	77	4.27	1.85	10	2.43	1286	<1	1.44	42	850	32	<5	<20	367	0.17	<10	156	<10	7	80	
150	S07-34045	0.7	4.69	15	930	<5	3.32	1	9	170	74	2.37	1.96	20	1.59	776	4	0.41	62	410	30	<5	<20	273	0.16	<10	159	<10	5	164	
159	S07-34054	1.0	3.91	30	615	<5	3.03	<1	8	283	68	2.36	1.47	10	1.42	906	<1	0.53	68	320	24	<5	<20	263	0.11	<10	67	<10	6	105	
Resplit:																															
1	S07-33896	0.6	5.95	20	440	<5	3.04	1	8	107	72	2.26	1.88	20	1.47	665	9	1.12	32	680	32	<5	<20	178	0.12	<10	240	<10	7	147	
36	S07-33931	0.8	7.92	15	495	<5	4.71	<1	17	65	128	5.14	2.02	10	1.77	990	<1	3.14	16	1260	30	<5	<20	382	0.22	<10	191	<10	8	56	
71	S07-33966	0.4	8.13	15	2770	<5	3.23	<1	23	70	75	5.09	1.56	10	2.94	1575	<1	3.01	30	990	28	<5	<20	482	0.18	<10	178	<10	6	53	
106	S07-34001	0.8	7.89	15	1180	<5	3.45	<1	20	60	115	5.38	0.92	10	2.37	1030	<1	3.54	25	1070	30	<5	<20	425	0.23	<10	200	<10	7	64	
141	S07-34036	0.8	6.97	20	3010	<5	3.70	<1	17	103	99	4.35	1.94	20	2.55	1306	<1	1.57	47	850	32	<5	<20	393	0.17	<10	162	<10	7	70	
176	S07-34071	0.6	3.97	10	800	<5	2.14	<1	7	388	60	2.44	1.48	10	1.50	636	<1	0.22	56	310	28	<5	<20	199	0.07	<10	72	<10	4	82	
Standard:																															
Stsd3		0.5	5.80	20	1235	<5	2.69	<1	14	57	40	3.98	1.53	30	1.36	2537	5	1.14	32	1610	58	<5	<20	256	0.31	<10	103	<10	28	196	
Stsd3		0.4	5.77	25	1325	<5	2.67	<1	15	58	35	4.10	1.51	40	1.34	2485	5	1.13	32	1650	60	<5	<20	277	0.34	<10	112	<10	28	198	
Stsd3		0.4	5.79	20	1295	<5	2.67	1	15	57	38	4.24	1.58	30	1.32	2454	5	1.12	31	1710	58	<5	<20	294	0.34	<10	110	<10	28	202	
Stsd3		0.5	5.82	20	1320	<5	2.75	<1	16	60	36	4.11	1.51	40	1.43	2589	5	1.11	33	1710	60	<5	<20	264	0.32	<10	108	<10	29	192	
Stsd3		0.5	5.77	25	1420	<5	2.70	<1	16	61	38	4.12	1.42	40	1.40	2644	5	1.19	35	1820	64	<5	<20	286	0.34	<10	118	<10	32	192	
Stsd3		0.4	5.71	25	1405	<5	2.69	<1	17	63	37	4.11	1.38	40	1.49	2659	6	1.17	36	1700	56	<5	<20	287	0.36	<10	118	<10	31	198	

ICP: 4 ACID DIGEST/ICP-FINISH
 AG: 4 ACID DIGEST/AA-FINISH

JJ/nw
 dl/td2271as/td2271bs
 XLS/07


 ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2275

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

5-Mar-08

Attention: Bob Singh

No. of samples received: 66
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-139
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-04953	<0.03	<0.001
2	S07-04954	<0.03	<0.001
3	S07-04955	<0.03	<0.001
4	S07-04956	<0.03	<0.001
5	S07-04957	<0.03	<0.001
6	S07-04958	<0.03	<0.001
7	S07-04959	<0.03	<0.001
8	S07-04960	<0.03	<0.001
9	S07-04961	<0.03	<0.001
10	S07-04962	<0.03	<0.001
11	S07-04963	0.05	0.001
12	S07-04964	<0.03	<0.001
13	S07-04965	<0.03	<0.001
14	S07-04966	0.43	0.013
15	S07-04967	0.09	0.003
16	S07-04968	0.05	0.001
17	S07-04969	0.06	0.002
18	S07-04970	0.08	0.002
19	S07-04971	0.09	0.002
20	S07-04972	0.09	0.002
21	S07-04973	0.07	0.002
22	S07-04974	0.05	0.001
23	S07-04975	<0.03	<0.001
24	S07-04976	<0.03	<0.001
25	S07-04977	<0.03	<0.001
26	S07-04978	<0.03	<0.001
27	S07-04979	<0.03	<0.001
28	S07-04980	0.03	0.001
29	S07-04981	0.04	0.001
30	S07-04982	<0.03	<0.001

* = 30g FA

ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
31	S07-04983	<0.03	<0.001
32	S07-04984	<0.03	<0.001
33	S07-04985	0.16	0.005
34	S07-04986	0.19	0.006
35	S07-04987	* <0.03	<0.001
36	S07-04988	0.13	0.004
37	S07-04989	0.18	0.005
38	S07-04990	0.48	0.014
39	S07-04991	0.54	0.016
40	S07-04992	<0.03	<0.001
41	S07-04993	0.14	0.004
42	S07-04994	0.36	0.010
43	S07-04995	0.09	0.003
44	S07-04996	0.08	0.002
45	S07-04997	* 2.00	0.058
46	S07-04998	<0.03	<0.001
47	S07-04999	<0.03	<0.001
48	S07-05000	<0.03	<0.001
49	S07-05001	0.03	0.001
50	S07-05002	0.05	0.002
51	S07-05003	0.15	0.004
52	S07-05004	<0.03	<0.001
53	S07-05005	0.50	0.015
54	S07-05006	0.75	0.022
55	S07-05007	1.39	0.041
56	S07-05008	0.49	0.014
57	S07-05009	0.20	0.006
58	S07-05010	0.33	0.010
59	S07-05011	0.20	0.006
60	S07-05012	* 0.44	0.013
61	S07-05013	1.60	0.047
62	S07-05014	0.38	0.011
63	S07-05015	0.52	0.015
64	S07-05016	0.87	0.025
65	S07-05017	0.20	0.006
66	S07-05018	0.10	0.003

QC DATA:**Resplit:**

1	S07-04953	<0.03	<0.001
36	S07-04988	0.15	0.005

* = 30g FA



ECO TECH LABORATORY LTD.

 Jutta Jealous
 B.C. Certified Assayer

Skygold Ventures AK7-2275

5-Mar-08

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
Standard:			
OXI54		1.86	0.054
OXI54		1.90	0.055
OXI54		1.90	0.055
OXI54		1.90	0.055
OXI54		1.88	0.055
OXI54		1.86	0.054

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw

XLS/07



ECO TECH LABORATORY LTD.

Jutta Jealouse

B.C. Certified Assayer

O TECH LABORATORY LTD.

341 Dallas Drive
 MLOOPS, B.C.
 C 6T4

Phone: 250-573-5700

Fax: 250-573-4557

ICP CERTIFICATE OF ANALYSIS ANALYST: J-2275

Skygold Ventures

615 - 800 W. Pender Street
 Vancouver, BC
 V6B 2V6

No. of samples received: 66

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-139

Samples submitted by: Tasha Gainer


Values in ppm unless otherwise reported

It #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-04953	0.6	4.94	15	655	<5	0.62	<1	7	182	25	2.02	1.79	<10	0.91	1355	<1	0.93	18	280	22	<5	<20	69	0.15	<10	30	<10	14	39
2	S07-04954	0.2	5.54	10	905	<5	0.69	<1	6	134	23	2.04	2.25	10	1.11	1561	<1	0.86	14	300	22	<5	<20	76	0.16	<10	24	<10	13	55
3	S07-04955	<0.2	5.66	5	885	<5	0.72	<1	6	139	21	2.00	2.26	10	1.15	1526	<1	0.82	13	300	22	<5	<20	74	0.17	<10	23	<10	15	58
4	S07-04956	0.6	5.69	115	765	<5	1.64	<1	15	387	65	3.77	2.37	10	2.22	1250	<1	0.34	94	450	24	<5	<20	96	0.13	<10	54	<10	10	58
5	S07-04957	0.4	4.24	365	65	<5	4.50	<1	40	1020	76	5.13	0.82	<10	4.23	1664	2	0.46	394	580	18	15	<20	145	0.05	<10	95	<10	6	84
6	S07-04958	0.4	4.88	325	50	<5	5.10	<1	37	1018	85	5.74	0.55	<10	5.56	1778	2	0.47	408	930	22	15	<20	173	0.07	<10	140	<10	6	100
7	S07-04959	0.6	4.71	80	30	<5	4.53	<1	31	484	21	4.46	0.43	<10	6.23	997	<1	0.64	235	630	18	<5	<20	187	0.07	<10	102	<10	7	53
8	S07-04960	0.6	3.94	90	55	<5	5.18	<1	28	471	124	3.88	0.82	<10	6.06	986	<1	0.57	217	540	16	5	<20	229	0.05	<10	77	<10	5	37
9	S07-04961	0.6	5.35	115	330	<5	3.93	<1	19	379	21	4.39	2.10	<10	4.22	1132	<1	0.46	106	880	18	10	<20	223	0.11	<10	102	<10	7	59
10	S07-04962	0.2	4.51	65	345	<5	3.20	<1	24	418	46	4.38	1.87	<10	4.60	1311	<1	0.32	156	650	18	5	<20	185	0.10	<10	97	<10	6	55
11	S07-04963	1.4	3.80	185	330	<5	4.00	<1	26	683	52	4.14	1.59	<10	2.85	1909	1	0.23	210	540	94	15	<20	169	0.05	<10	105	<10	4	68
12	S07-04964	1.2	5.26	170	765	<5	1.79	<1	17	304	101	4.66	2.42	20	0.70	1703	3	0.17	79	520	32	10	<20	84	0.11	<10	137	<10	6	69
13	S07-04965	0.6	4.18	95	530	<5	3.14	<1	16	355	97	3.81	1.96	10	1.74	1100	1	0.12	85	530	26	5	<20	152	0.08	<10	94	<10	5	78
14	S07-04966	1.0	5.98	95	375	<5	0.27	<1	8	26	32	3.15	4.47	10	0.34	177	3	0.10	16	510	22	40	<20	55	0.39	<10	69	<10	12	49
15	S07-04967	1.0	5.00	195	370	<5	2.18	1	25	293	185	5.82	2.34	20	1.19	753	18	0.14	121	1020	64	5	<20	140	0.10	<10	254	<10	8	239
16	S07-04968	0.8	5.17	250	370	<5	2.10	2	30	389	69	5.98	2.27	20	1.11	1126	27	0.15	168	1080	56	5	<20	155	0.09	<10	264	<10	9	302
17	S07-04969	1.0	5.62	265	420	<5	1.42	1	28	331	95	5.83	2.58	20	0.86	689	29	0.17	167	1230	58	10	<20	111	0.08	<10	292	<10	9	374
18	S07-04970	1.4	5.42	325	475	<5	2.05	<1	32	331	91	5.76	2.04	20	1.08	740	41	0.12	222	1150	52	10	<20	129	0.10	<10	271	<10	11	388
19	S07-04971	1.4	4.59	265	330	<5	2.09	2	30	319	76	6.15	2.10	20	1.05	844	27	0.11	180	1070	50	10	<20	129	0.07	<10	240	<10	7	325
20	S07-04972	1.6	5.21	110	310	<5	2.36	2	23	302	97	5.40	2.41	20	1.18	874	26	0.14	118	980	44	10	<20	142	0.08	<10	254	<10	7	217
21	S07-04973	1.4	4.97	40	175	<5	3.83	3	22	249	65	5.44	2.34	20	1.85	973	27	0.13	105	1000	42	5	<20	210	0.07	<10	250	<10	7	167
22	S07-04974	1.0	4.55	30	180	<5	4.99	3	19	257	87	4.75	2.15	20	2.35	1210	22	0.18	97	930	36	5	<20	272	0.07	<10	227	<10	7	145
23	S07-04975	0.6	4.41	60	285	<5	4.44	1	37	717	97	5.31	1.78	10	3.96	1363	12	0.36	261	1330	32	10	<20	276	0.07	<10	171	<10	7	143
24	S07-04976	0.4	4.28	70	265	<5	2.49	<1	23	547	45	3.37	1.41	<10	3.82	1216	3	0.86	185	420	24	10	<20	173	0.07	<10	62	<10	7	67
25	S07-04977	1.0	5.09	25	370	<5	2.17	<1	18	326	48	3.19	1.93	<10	3.92	1352	<1	0.76	122	570	160	10	<20	170	0.08	<10	65	<10	8	58


Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La ...%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	w	Y	Zn	
QC DATA:																														
Repeat:																														
1	S07-04953	0.4	4.89	15	670	<5	0.64	<1	7	199	25	2.05	1.86	<10	0.94	1353	<1	0.94	18	270	20	<5	<20	72	0.15	<10	29	<10	12	42
10	S07-04962	0.4	4.39	65	340	<5	3.10	<1	23	418	47	4.24	1.86	<10	4.57	1274	<1	0.32	147	630	18	5	<20	185	0.10	<10	95	<10	7	53
19	S07-04971	1.4	4.52	260	325	<5	2.07	2	30	316	76	5.96	2.05	20	1.05	839	27	0.11	179	1070	52	10	<20	128	0.07	<10	235	<10	6	323
36	S07-04988	2.2	4.40	25	220	<5	3.90	6	23	270	70	4.80	1.88	20	1.11	1165	35	0.30	91	3020	58	10	<20	200	0.10	<10	300	<10	11	333
46	S07-04998	0.4	7.10	5	740	<5	3.35	<1	14	134	44	3.92	2.15	10	2.06	1126	1	2.35	20	770	30	<5	<20	262	0.13	<10	139	<10	6	57
54	S07-05006	0.4	6.03	5	245	<5	2.19	<1	11	304	77	3.33	2.59	20	1.29	597	9	0.61	40	730	30	<5	<20	178	0.15	<10	230	<10	7	79
Resplit:																														
1	S07-04953	0.4	5.00	15	700	<5	0.65	<1	7	179	25	1.84	1.88	10	0.85	1329	<1	1.04	19	290	20	<5	<20	75	0.15	<10	31	<10	11	40
36	S07-04988	1.8	4.40	15	265	<5	3.90	3	23	270	70	4.20	2.04	10	1.03	1203	31	0.69	87	3120	58	5	<20	204	0.13	<10	291	<10	13	328
Standard:																														
3std3		0.5	5.68	20	1340	<5	2.39	<1	15	58	35	4.12	1.37	30	1.37	2612	5	1.20	33	1600	54	<5	<20	277	0.33	<10	119	<10	27	199
3std3		0.5	5.77	20	1355	<5	2.38	<1	15	60	35	4.04	1.38	30	1.38	2596	5	1.20	33	1630	54	<5	<20	273	0.34	<10	111	<10	28	194

CP: 4 ACID DIGEST/ICP-FINISH
 AG: 4 ACID DIGEST/AA-FINISH

1J/nw
 1td2275s
 1LS/07



ECO TECH LABORATORY LTD.
 Julia Jalouse
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2276

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC


10-Mar-08

Attention: Bob Singh

No. of samples received: 98
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-140
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-05019	<0.03	<0.001
2	S07-05020	<0.03	<0.001
3	S07-05021	<0.03	<0.001
4	S07-05022	<0.03	<0.001
5	S07-05023	0.03	0.001
6	S07-05024	<0.03	<0.001
7	S07-05025	0.37	0.011
8	S07-05026	<0.03	<0.001
9	S07-05027	0.16	0.005
10	S07-05028	1.63	0.048
11	S07-05029	0.32	0.009
12	S07-05030	0.76	0.022
13	S07-05031	0.56	0.016
14	S07-05032	<0.03	<0.001
15	S07-05033	0.03	0.001
16	S07-05034	<0.03	<0.001
17	S07-05035	0.05	0.002
18	S07-05036	0.14	0.004
19	S07-05037	0.13	0.004
20	S07-05038	0.16	0.005
21	S07-05039	0.07	0.002
22	S07-05040	0.04	0.001
23	S07-05041	0.04	0.001
24	S07-05042	<0.03	<0.001
25	S07-05043	0.37	0.011
26	S07-05044	0.06	0.002
27	S07-05045	0.09	0.003
28	S07-05046	0.18	0.005


ECOTECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	S07-05047	0.03	0.001
30	S07-05048	0.06	0.002
31	S07-05049	<0.03	<0.001
32	S07-05050	<0.03	<0.001
33	S07-05051	0.17	0.005
34	S07-05052	0.13	0.004
35	S07-05053	<0.03	<0.001
36	S07-05054	<0.03	<0.001
37	S07-05055	<0.03	<0.001
38	S07-05056	0.20	0.006
39	S07-05057	*	2.08 0.061
40	S07-05058	1.18	0.035
41	S07-05059	0.14	0.004
42	S07-05060	0.08	0.002
43	S07-05061	0.05	0.001
44	S07-05062	<0.03	<0.001
45	S07-05063	<0.03	<0.001
46	S07-05064	0.24	0.007
47	S07-05065	0.06	0.002
48	S07-05066	*	<0.03 <0.001
49	S07-05067	<0.03	<0.001
50	S07-05068	<0.03	<0.001
51	S07-05069	0.05	0.001
52	S07-05070	0.03	0.001
53	S07-05071	<0.03	<0.001
54	S07-05072	<0.03	<0.001
55	S07-05073	<0.03	<0.001
56	S07-05074	<0.03	<0.001
57	S07-05075	<0.03	<0.001
58	S07-05076	<0.03	<0.001
59	S07-05077	<0.03	<0.001
60	S07-05078	0.07	0.002
61	S07-05079	<0.03	<0.001
62	S07-05080	<0.03	<0.001
63	S07-05081	<0.03	<0.001
64	S07-05082	<0.03	<0.001
65	S07-05083	0.56	0.016
66	S07-05084	<0.03	<0.001
67	S07-05085	*	<0.03 <0.001
68	S07-05086	0.05	0.002
69	S07-05087	<0.03	<0.001
70	S07-05088	<0.03	<0.001
71	S07-05089	<0.03	<0.001



ECO TECH LABORATORY LTD.

Julie Jealouse

B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
72	S07-05090	<0.03	<0.001
73	S07-05091	<0.03	<0.001
74	S07-05092	<0.03	<0.001
75	S07-05093	<0.03	<0.001
76	S07-05094	<0.03	<0.001
77	S07-05095	<0.03	<0.001
78	S07-05096	<0.03	<0.001
79	S07-05097	<0.03	<0.001
80	S07-05098	<0.03	<0.001
81	S07-05099	<0.03	<0.001
82	S07-05100	<0.03	<0.001
83	S07-05101	<0.03	<0.001
84	S07-05102	<0.03	<0.001
85	S07-05103	<0.03	<0.001
86	S07-05104	0.43	0.013
87	S07-05105	0.15	0.004
88	S07-05106	0.11	0.003
89	S07-05107	0.15	0.004
90	S07-05108	0.92	0.027
91	S07-05109	0.06	0.002
92	S07-05110	0.22	0.006
93	S07-05111	0.24	0.007
94	S07-05112	1.17	0.034
95	S07-05113	0.35	0.010
96	S07-05114	0.23	0.007
97	S07-05115	0.19	0.006
98	S07-05116	0.17	0.005

QC DATA:

Resplit:

1	S07-05019	<0.03	<0.001
36	S07-05054	<0.03	<0.001
71	S07-05089	<0.03	<0.001


Standard:

OXI54	1.89	0.055
OXI54	1.90	0.055
OXI54	1.88	0.055
OXI54	1.88	0.055
OXI54	1.89	0.055
OXI54	1.85	0.054
OXI54	1.89	0.055
OXI54	1.84	0.054

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw
XLS/07



ECO TECH LABORATORY LTD.

Julia Jealouse
B.C. Certified Assayer

DO TECH LABORATORY LTD.

1041 Dallas Drive

AMLOOPS, B.C.

2C 6T4

Phone: 250-573-5700

Fax: 250-573-4557

ICP CERTIFICATE OF ANALYSIS ANAL-007-2276

Skygold Ventures

615 - 800 W. Pender Street

Vancouver, BC

V6B 2V6

No. of samples received: 98

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-140

Samples submitted by: Tasha Gainer


Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-05019	0.6	4.74	180	620	<5	1.27	<1	28	282	83	4.47	1.43	20	0.34	2414	3	1.29	133	500	28	5	<20	76	0.11	<10	106	<10	6	159
2	S07-05020	0.6	8.59	130	1895	<5	1.09	<1	27	94	109	3.87	2.95	20	0.93	1951	<1	1.37	91	940	38	10	<20	98	0.17	<10	178	<10	10	136
3	S07-05021	<0.2	7.08	5	575	<5	2.78	<1	10	83	40	4.32	1.05	10	1.32	769	3	2.58	28	800	24	<5	<20	310	0.36	<10	106	<10	17	48
4	S07-05022	0.4	4.64	200	675	<5	1.43	<1	24	275	50	4.11	1.72	20	0.87	2264	1	0.72	130	510	24	10	<20	102	0.08	<10	102	<10	5	148
5	S07-05023	0.6	4.86	100	585	<5	0.13	<1	17	217	104	4.81	1.52	30	0.16	648	4	0.99	69	550	28	<5	<20	50	0.10	<10	116	<10	5	163
6	S07-05024	0.4	5.06	60	865	<5	1.66	<1	14	277	55	3.06	2.10	10	1.09	1923	2	0.23	55	540	20	5	<20	116	0.07	<10	106	<10	8	119
7	S07-05025	0.4	5.71	10	895	<5	2.87	<1	9	138	84	3.08	2.12	20	1.69	860	3	0.66	28	930	30	<5	<20	198	0.11	<10	111	<10	8	127
8	S07-05026	0.4	6.56	<5	1190	<5	0.94	<1	8	71	40	2.65	2.43	20	1.51	306	1	1.09	16	650	24	<5	<20	96	0.14	<10	100	<10	9	83
9	S07-05027	0.2	5.94	10	790	<5	1.47	<1	10	121	48	3.21	2.44	20	1.39	365	19	0.60	23	520	28	<5	<20	107	0.11	<10	107	<10	7	82
10	S07-05028	0.2	4.93	5	820	<5	1.44	1	7	129	82	2.41	1.92	10	1.03	428	12	0.85	32	590	18	<5	<20	111	0.11	<10	201	<10	6	146
11	S07-05029	0.6	6.82	10	530	<5	3.27	2	16	169	108	4.71	2.30	20	1.68	718	12	1.43	37	790	32	<5	<20	208	0.18	<10	335	<10	9	193
12	S07-05030	0.8	5.90	20	560	<5	2.86	3	22	187	79	6.15	2.17	20	1.35	684	26	1.22	51	760	28	<5	<20	168	0.15	<10	346	<10	6	277
13	S07-05031	0.4	5.42	15	415	<5	3.36	<1	14	201	77	5.08	1.72	20	1.46	813	11	1.49	36	950	28	<5	<20	204	0.12	<10	164	<10	6	99
14	S07-05032	0.4	5.38	15	515	<5	3.77	<1	14	234	74	4.14	1.72	20	1.83	940	8	1.53	29	900	26	<5	<20	236	0.12	<10	169	<10	8	91
15	S07-05033	0.4	7.54	15	760	<5	3.68	<1	19	131	82	5.56	2.34	10	2.53	814	8	1.96	25	980	44	<5	<20	261	0.16	<10	230	<10	7	137
16	S07-05034	0.4	7.88	10	765	<5	3.54	<1	23	143	89	5.87	2.42	10	2.58	824	6	2.00	26	1050	42	<5	<20	257	0.17	<10	233	<10	8	137
17	S07-05035	0.6	5.56	15	460	<5	3.38	1	18	167	74	5.46	1.93	20	1.53	645	15	1.16	38	1290	28	<5	<20	188	0.14	<10	243	<10	9	166
18	S07-05036	0.2	3.45	5	445	<5	2.31	<1	6	275	43	2.75	1.13	10	1.16	645	4	0.96	20	520	18	<5	<20	173	0.08	<10	69	<10	6	59
19	S07-05037	0.2	7.98	10	1280	<5	3.14	<1	10	125	49	3.40	2.54	30	1.85	617	2	0.91	18	630	32	<5	<20	231	0.13	<10	106	<10	11	99
20	S07-05038	0.2	4.84	10	570	<5	3.30	<1	9	152	50	2.95	1.57	20	1.47	968	1	1.39	22	620	22	<5	<20	216	0.11	<10	72	<10	8	44
21	S07-05039	<0.2	6.68	10	910	<5	5.01	<1	7	136	43	3.24	2.14	20	2.13	1373	<1	1.95	10	820	30	<5	<20	256	0.11	<10	79	110	9	67
22	S07-05040	0.2	6.55	5	805	<5	3.27	<1	10	104	50	3.03	1.99	20	1.41	648	2	1.92	12	630	28	<5	<20	205	0.11	<10	85	<10	9	70
23	S07-05041	0.2	6.24	<5	1430	<5	2.16	<1	7	104	36	2.55	2.42	20	1.16	424	3	1.09	9	400	32	<5	<20	142	0.12	<10	58	<10	9	65
24	S07-05042	<0.2	6.81	10	1680	<5	2.66	<1	6	67	22	2.20	2.64	20	1.23	670	6	1.44	6	690	24	<5	<20	165	0.16	<10	55	<10	9	41
25	S07-05043	0.6	6.59	10	745	<5	2.88	<1	13	98	60	4.11	2.24	20	1.31	645	3	1.51	17	630	32	<5	<20	172	0.16	<10	120	<10	9	81


#.	Tag #	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	W	Zn			
0	S07-05098	<0.2	7.26	<5	655	<5	3.14	<1	12	71	60	3.57	1.58	20	1.32	831	<1	1.89	12	670	28	<5	<20	426	0.18	<10	114	<10	6	78
9	S07-05107	0.8	8.79	10	730	<5	3.39	<1	21	59	200	6.89	2.52	20	2.07	1118	<1	1.79	15	2090	42	<5	<20	335	0.29	<10	242	<10	12	67
plit:																														
1	S07-05019	0.4	4.92	190	635	<5	1.38	<1	31	310	78	4.69	1.57	20	0.41	2462	3	1.21	147	540	30	5	<20	81	0.11	<10	110	<10	6	160
6	S07-05054	0.6	7.49	15	785	<5	3.27	<1	17	97	108	4.99	1.68	10	1.71	1219	<1	2.16	29	880	36	<5	<20	388	0.23	<10	160	<10	6	81
1	S07-05089	<0.2	8.55	<5	670	<5	4.13	<1	12	25	47	4.16	1.58	10	1.79	1256	<1	2.29	13	940	34	<5	<20	643	0.20	<10	130	<10	5	89
idard:																														
3		0.5	5.54	25	1255	<5	2.46	<1	15	60	38	4.17	1.57	40	1.28	2521	5	1.26	33	1730	60	5	<20	236	0.34	<10	107	<10	28	205
3		0.4	5.55	25	1250	<5	2.34	<1	15	61	38	4.21	1.59	30	1.26	2482	5	1.28	33	1740	58	<5	<20	249	0.34	<10	113	<10	29	200
3		0.5	5.60	20	1295	<5	2.43	<1	15	60	37	4.26	1.67	40	1.20	2560	5	1.25	33	1710	60	<5	<20	231	0.33	<10	107	<10	28	201

4 ACID DIGEST/ICP-FINISH
4 ACID DIGEST/AA-FINISH

w
276s
/07



ECO TECH LABORATORY LTD.
Jutta J. House
B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2251

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC


27-Feb-08

Attention: Bob Singh

No. of samples received: 123
Sample Type: Core
Project: **Spanish Mountain**
Shipment #: **SMC-07-141**
Samples submitted by: Tasha Gainer

ET #.	Tag #	Metallic Assays	
		Au (g/t)	Au (oz/t)
1	S07-05117	* <0.03	<0.001
2	S07-05118	<0.03	<0.001
3	S07-05119	<0.03	<0.001
4	S07-05120	<0.03	<0.001
5	S07-05121	<0.03	<0.001
6	S07-05122	<0.03	<0.001
7	S07-05123	<0.03	<0.001
8	S07-05124	<0.03	<0.001
9	S07-05125	<0.03	<0.001
10	S07-05126	<0.03	<0.001
11	S07-05127	<0.03	<0.001
12	S07-05128	<0.03	<0.001
13	S07-05129	<0.03	<0.001
14	S07-05130	<0.03	<0.001
15	S07-05131	<0.03	<0.001
16	S07-05132	<0.03	<0.001
17	S07-05133	<0.03	<0.001
18	S07-05134	<0.03	<0.001
19	S07-05135	<0.03	<0.001
20	S07-05136	<0.03	<0.001
21	S07-05137	<0.03	<0.001
22	S07-05138	<0.03	<0.001
23	S07-05139	<0.03	<0.001
24	S07-05140	* 2.08	0.061
25	S07-05141	<0.03	<0.001
26	S07-05142	<0.03	<0.001

* = 30g FA


ECOTECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
27	S07-05143	<0.03	<0.001
28	S07-05144	<0.03	<0.001
29	S07-05145	<0.03	<0.001
30	S07-05146	<0.03	<0.001
31	S07-05147	0.11	0.003
32	S07-05148	0.06	0.002
33	S07-05149	<0.03	<0.001
34	S07-05150	<0.03	<0.001
35	S07-05151	<0.03	<0.001
36	S07-05152	<0.03	<0.001
37	S07-05153	<0.03	<0.001
38	S07-05154	* <0.03	<0.001
39	S07-05155	<0.03	<0.001
40	S07-05156	<0.03	<0.001
41	S07-05157	<0.03	<0.001
42	S07-05158	0.03	0.001
43	S07-05159	<0.03	<0.001
44	S07-05160	<0.03	<0.001
45	S07-05161	<0.03	<0.001
46	S07-05162	* 2.05	0.060
47	S07-05163	<0.03	<0.001
48	S07-05164	<0.03	<0.001
49	S07-05165	<0.03	<0.001
50	S07-05166	<0.03	<0.001
51	S07-05167	0.09	0.003
52	S07-05168	<0.03	<0.001
53	S07-05169	<0.03	<0.001
54	S07-05170	<0.03	<0.001
55	S07-05171	<0.03	<0.001
56	S07-05172	<0.03	<0.001
57	S07-05173	0.06	0.002
58	S07-05174	0.20	0.006
59	S07-05175	0.36	0.011
60	S07-05176	0.08	0.002
61	S07-05177	<0.03	<0.001
62	S07-05178	<0.03	<0.001
63	S07-05179	<0.03	<0.001
64	S07-05180	0.04	0.001
65	S07-05181	0.05	0.001
66	S07-05182	<0.03	<0.001
67	S07-05183	0.03	0.001
68	S07-05184	0.03	0.001
69	S07-05185	<0.03	<0.001
70	S07-05186	<0.03	<0.001
71	S07-05187	0.03	0.001
72	S07-05188	* <0.03	<0.001
73	S07-05189	<0.03	<0.001

* = 30g FA




ECO TECH LABORATORY LTD.

 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
74	S07-05190	<0.03	<0.001
75	S07-05191	<0.03	<0.001
76	S07-05192	<0.03	<0.001
77	S07-05193	<0.03	<0.001
78	S07-05194	<0.03	<0.001
79	S07-05195	<0.03	<0.001
80	S07-05196	<0.03	<0.001
81	S07-05197	<0.03	<0.001
82	S07-05198	* 2.10	0.061
83	S07-05199	<0.03	<0.001
84	S07-05200	<0.03	<0.001
85	S07-05201	<0.03	<0.001
86	S07-05202	<0.03	<0.001
87	S07-05203	0.10	0.003
88	S07-05204	0.04	0.001
89	S07-05205	<0.03	<0.001
90	S07-05206	<0.03	<0.001
91	S07-05207	0.12	0.003
92	S07-05208	<0.03	<0.001
93	S07-05209	<0.03	<0.001
94	S07-05210	<0.03	<0.001
95	S07-05211	<0.03	<0.001
96	S07-05212	0.06	0.002
97	S07-05213	<0.03	<0.001
98	S07-05214	<0.03	<0.001
99	S07-05215	<0.03	<0.001
100	S07-05216	<0.03	<0.001
101	S07-05217	<0.03	<0.001
102	S07-05218	0.19	0.005
103	S07-05219	0.04	0.001
104	S07-05220	0.25	0.007
105	S07-05221	0.23	0.007
106	S07-05222	0.41	0.012
107	S07-05223	0.13	0.004
108	S07-05224	0.37	0.011
109	S07-05225	0.38	0.011
110	S07-05226	0.35	0.010
111	S07-05227	0.08	0.002
112	S07-05228	0.09	0.003
113	S07-05229	0.61	0.018
114	S07-05230	0.92	0.027
115	S07-05231	0.31	0.009
116	S07-05232	0.24	0.007
117	S07-05233	0.16	0.005
118	S07-05234	* <0.03	<0.001

* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
119	S07-05235	0.18	0.005
120	S07-05236	0.82	0.024
121	S07-05237	1.01	0.029
122	S07-05238	0.30	0.009
123	S07-05239	<0.03	<0.001

QC DATA:

Resplit:

2	S07-05118	0.04	0.001
36	S07-05152	<0.03	<0.001
71	S07-05187	<0.03	<0.001
106	S07-05222	0.36	0.010


Standard:

OXi54	1.80	0.052
OXi54	1.85	0.054
OXi54	1.86	0.054
OXi54	1.82	0.053
OXi54	1.90	0.055
Xi54	1.83	0.053
JXi54	1.82	0.053
OXi54	1.87	0.055
OXi54	1.90	0.055
OXi54	1.80	0.052

* = 30g FA

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

JJ/sa
XLS/07


ECOTECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

TECH LABORATORY LTD.

41 Dallas Drive

MLOOPS, B.C.

V6T4

Phone: 250-573-5700

Fax: 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK-07-2251

Skygold Ventures

615 - 800 W. Pender Street

Vancouver, BC

V6B 2V6

No. of samples received: 123

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-141

Samples submitted by: Tasha Gainer

Concentrations in ppm unless otherwise reported

#.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-05117	<0.2	0.04	<5	<5	<5	>10	<1	<1	<1	3	0.04	<0.01	<10	1.68	21	<1	0.02	23	30	4	<5	<20	5728	<0.01	<10	5	<10	<1	2
2	S07-05118	0.5	6.54	<5	705	<5	3.39	<1	9	36	128	4.61	1.92	20	1.43	856	<1	1.93	7	1060	24	<5	<20	510	0.18	<10	146	<10	8	54
3	S07-05119	0.4	6.53	<5	865	<5	2.82	<1	9	62	46	3.04	2.12	20	0.99	648	<1	2.18	7	590	20	<5	<20	411	0.12	<10	90	<10	6	33
4	S07-05120	0.4	6.96	<5	815	<5	2.60	<1	7	107	44	2.95	2.11	20	0.78	699	<1	2.40	8	470	24	5	<20	418	0.12	<10	69	<10	5	41
5	S07-05121	0.4	6.65	<5	800	<5	2.58	<1	6	79	40	2.92	2.12	10	0.87	712	<1	2.52	7	490	26	<5	<20	539	0.11	<10	67	<10	5	32
6	S07-05122	0.4	6.36	<5	635	<5	3.57	<1	8	107	55	3.19	1.78	10	1.04	890	<1	2.42	9	500	26	5	<20	727	0.12	<10	107	<10	5	37
7	S07-05123	0.4	5.86	<5	605	<5	2.75	<1	7	50	43	2.99	1.78	10	1.06	699	<1	2.99	6	470	24	5	<20	462	0.11	<10	103	<10	6	42
8	S07-05124	0.6	5.80	<5	645	<5	2.70	<1	14	47	55	2.88	2.17	10	1.02	689	<1	2.66	7	450	22	5	<20	441	0.11	<10	105	<10	5	42
9	S07-05125	4.8	6.16	<5	790	<5	4.15	<1	15	70	87	4.13	2.85	10	1.56	992	<1	2.91	19	1060	28	10	<20	446	0.19	<10	159	<10	8	68
0	S07-05126	0.8	6.77	<5	775	<5	3.28	<1	17	78	143	5.71	2.65	10	2.07	1150	<1	2.49	23	1080	30	10	<20	571	0.17	<10	232	<10	6	76
1	S07-05127	0.6	7.71	<5	790	<5	2.93	<1	22	42	146	6.90	2.63	10	2.36	1244	<1	2.64	17	1030	36	10	<20	634	0.17	<10	254	<10	5	60
2	S07-05128	0.8	7.02	<5	1155	<5	3.56	<1	22	57	106	5.34	3.01	<10	2.05	1356	<1	2.22	18	840	32	15	<20	625	0.17	<10	270	<10	4	60
3	S07-05129	0.6	6.39	<5	1050	<5	3.29	<1	13	55	127	4.45	3.07	20	1.62	1048	<1	2.59	11	850	32	10	<20	663	0.16	<10	180	<10	6	57
4	S07-05130	0.2	6.51	5	815	<5	3.83	<1	9	62	49	3.19	2.29	20	1.18	851	<1	2.01	9	670	26	<5	<20	526	0.14	<10	89	<10	6	47
5	S07-05131	0.2	6.10	5	1050	<5	3.00	<1	7	27	50	2.81	2.31	20	1.07	626	<1	1.77	9	530	24	<5	<20	454	0.16	<10	75	<10	6	40
6	S07-05132	0.4	6.10	5	1130	<5	3.03	<1	10	55	55	3.00	2.25	20	1.12	616	<1	1.81	12	510	24	<5	<20	350	0.17	<10	89	<10	5	45
7	S07-05133	0.8	5.81	5	1195	<5	2.30	<1	8	50	54	2.50	2.36	20	1.03	538	<1	1.87	10	460	26	<5	<20	337	0.14	<10	62	<10	6	29
8	S07-05134	0.6	6.18	<5	1130	<5	3.14	<1	8	25	78	2.94	2.32	20	1.06	617	<1	1.70	8	540	26	<5	<20	506	0.14	<10	70	<10	6	52
9	S07-05135	0.2	6.56	<5	665	<5	3.82	<1	9	39	55	3.43	1.76	20	1.16	775	<1	2.29	8	790	28	<5	<20	700	0.15	<10	90	<10	6	50
0	S07-05136	0.4	6.63	<5	850	<5	3.53	<1	6	25	46	2.77	2.03	20	0.88	728	<1	2.00	7	560	26	<5	<20	592	0.15	<10	60	<10	6	35
1	S07-05137	0.2	6.14	<5	760	<5	3.56	<1	5	42	36	2.60	2.06	20	0.81	690	<1	1.81	6	550	24	<5	<20	638	0.14	<10	54	<10	6	37
2	S07-05138	0.4	6.02	<5	720	<5	3.91	<1	7	45	55	2.62	1.87	20	0.81	674	<1	1.96	7	600	24	<5	<20	712	0.15	<10	71	<10	6	39
3	S07-05139	0.6	6.46	<5	795	<5	3.21	<1	8	45	106	3.76	2.03	20	1.09	781	<1	2.33	6	950	30	<5	<20	398	0.19	<10	113	<10	7	41
4	S07-05140	4.6	4.26	95	275	<5	0.45	2	11	39	577	5.25	2.27	20	1.68	376	7	0.26	21	510	94	45	<20	73	0.29	<10	56	<10	11	656
5	S07-05141	0.6	6.95	<5	825	<5	3.46	<1	18	43	237	6.76	2.00	20	1.74	1016	<1	2.57	10	1870	34	<5	<20	442	0.32	<10	238	<10	13	62
6	S07-05142	0.8	7.07	<5	510	<5	3.53	<1	18	62	274	7.10	1.52	20	1.93	957	<1	2.55	11	1810	30	<5	<20	593	0.30	<10	240	<10	15	69
7	S07-05143	1.0	7.47	<5	680	<5	3.44	<1	22	35	266	7.28	1.86	20	1.83	1010	<1	2.44	11	1910	28	<5	<20	617	0.28	<10	248	<10	14	66
8	S07-05144	0.8	6.29	5	310	<5	3.90	<1	21	49	215	7.12	1.17	20	1.77	1161	21	3.01	10	1940	26	<5	<20	480	0.27	<10	220	<10	14	66
9	S07-05145	0.8	5.98	10	385	<5	4.57	<1	20	54	206	7.23	1.69	20	1.84	1287	<1	2.68	11	1850	30	<5	<20	519	0.30	<10	230	<10	14	60
0	S07-05146	0.4	6.00	10	420	<5	2.97	<1	20	40	213	7.06	1.45	20	1.82	1030	<1	2.80	10	1910	24	<5	<20	499	0.33	<10	243	<10	14	61

t #.	Tag #	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn		
31	S07-05147	0.6	5.42	<5	415	<5	4.46	<1	17	82	189	7.03	1.38	20	1.87	1369	<1	2.39	10	1630	24	<5	<20	507	0.27	<10	204	<10	12	120
32	S07-05148	0.8	7.18	<5	460	<5	3.93	<1	24	46	298	7.68	1.40	20	2.07	1122	<1	3.66	10	2270	32	<5	<20	590	0.36	<10	268	<10	15	96
33	S07-05149	0.8	7.09	5	370	<5	3.76	<1	24	44	259	8.35	0.87	30	2.35	1166	2	2.53	11	2170	26	<5	<20	607	0.31	<10	271	<10	15	60
34	S07-05150	0.4	6.24	5	440	<5	3.97	<1	16	91	184	6.63	1.17	20	1.84	1146	<1	2.67	10	1720	26	<5	<20	546	0.32	<10	211	<10	12	78
35	S07-05151	0.2	5.62	5	215	<5	1.88	<1	9	56	64	3.78	0.59	20	1.09	629	<1	4.58	10	800	20	<5	<20	334	0.27	<10	119	<10	5	46
36	S07-05152	1.0	6.15	<5	1495	<5	2.21	<1	10	62	59	4.10	0.67	20	1.22	642	<1	4.18	11	800	24	<5	<20	429	0.25	<10	131	<10	6	52
37	S07-05153	1.2	7.07	5	625	<5	4.35	<1	18	62	146	6.12	1.38	10	1.98	1136	<1	1.92	14	1170	28	<5	<20	654	0.19	<10	206	<10	8	72
38	S07-05154	<0.2	0.06	<5	<5	<5	>10	<1	<1	2	2	0.05	<0.01	<10	1.68	21	<1	0.02	29	40	<2	<5	<20	5512	<0.01	<10	2	<10	<1	1
39	S07-05155	0.2	7.65	5	665	<5	4.26	<1	19	71	74	5.90	1.55	10	2.14	1191	<1	3.01	19	820	32	<5	<20	751	0.18	<10	202	<10	4	63
40	S07-05156	1.0	5.58	10	285	<5	3.31	<1	14	121	128	4.80	0.71	20	1.58	1043	<1	2.83	16	1230	22	<5	<20	565	0.25	<10	160	<10	9	49
41	S07-05157	0.6	5.42	<5	305	<5	3.34	<1	13	139	128	4.75	0.76	20	1.63	1073	<1	2.76	14	1200	22	<5	<20	580	0.20	<10	153	<10	8	54
42	S07-05158	0.6	6.74	5	515	<5	3.98	<1	17	81	160	6.77	1.74	20	1.74	1118	<1	2.29	11	1740	28	<5	<20	532	0.29	<10	225	<10	13	50
43	S07-05159	0.6	7.03	5	500	<5	4.00	<1	22	91	233	7.11	1.20	20	1.86	1069	7	2.72	11	1850	28	<5	<20	738	0.34	<10	247	<10	13	65
44	S07-05160	0.2	6.38	5	560	<5	3.34	<1	17	124	171	6.70	1.41	20	1.66	1093	1	2.13	11	1650	28	<5	<20	596	0.27	<10	217	<10	11	69
45	S07-05161	0.4	6.95	5	440	<5	3.82	<1	22	75	233	6.73	1.07	20	1.69	1032	<1	2.90	11	1790	28	<5	<20	816	0.28	<10	232	<10	12	65
46	S07-05162	4.4	4.21	105	290	<5	0.44	2	11	39	596	5.23	2.50	20	1.75	377	7	0.03	22	510	94	45	<20	70	0.29	<10	57	<10	12	670
47	S07-05163	0.4	7.35	5	455	<5	4.52	<1	20	91	253	6.56	1.23	10	1.82	943	2	2.78	12	1440	28	<5	<20	811	0.24	<10	245	<10	11	56
48	S07-05164	0.6	7.28	5	685	<5	3.96	<1	18	102	202	6.04	1.51	10	1.66	869	<1	2.90	12	1370	28	<5	<20	780	0.22	<10	193	<10	9	60
49	S07-05165	0.4	6.26	5	865	<5	3.12	<1	14	112	124	4.39	1.36	10	1.66	879	<1	2.88	11	950	26	<5	<20	680	0.22	<10	186	<10	9	45
50	S07-05166	<0.2	6.37	10	1625	<5	3.04	<1	11	105	55	4.65	1.70	10	1.69	902	<1	2.37	11	850	24	<5	<20	724	0.17	<10	127	<10	6	56
51	S07-05167	0.6	5.93	15	1050	<5	3.85	<1	15	154	105	4.93	1.55	20	2.37	1014	17	1.40	42	830	28	<5	<20	567	0.16	<10	295	<10	7	78
52	S07-05168	0.4	6.22	10	580	<5	3.61	<1	17	108	71	5.05	1.16	10	2.27	1250	<1	2.17	24	600	26	<5	<20	685	0.15	<10	176	<10	4	64
53	S07-05169	0.4	5.68	5	860	<5	3.12	<1	17	215	74	4.74	1.56	10	1.58	1209	1	1.88	22	870	24	<5	<20	416	0.15	<10	136	<10	5	70
54	S07-05170	0.2	6.50	5	735	<5	3.17	<1	16	120	45	5.01	1.29	10	2.14	1283	<1	2.36	22	640	28	<5	<20	701	0.15	<10	189	<10	4	69
55	S07-05171	<0.2	6.24	5	785	<5	5.22	<1	11	86	40	4.60	0.98	10	2.04	1240	<1	2.41	12	670	26	<5	<20	784	0.16	<10	120	<10	7	53
56	S07-05172	0.4	7.02	5	615	<5	3.45	<1	20	110	99	5.59	0.85	<10	2.29	1030	<1	3.16	20	800	26	<5	<20	700	0.17	<10	189	<10	5	59
57	S07-05173	0.8	6.42	15	1495	<5	4.61	<1	24	133	85	6.23	1.61	<10	3.24	1349	<1	1.70	31	870	32	<5	<20	548	0.14	<10	192	<10	6	77
58	S07-05174	1.8	5.30	10	175	<5	2.96	2	12	319	75	3.96	1.99	20	1.50	780	24	0.55	61	780	32	5	<20	253	0.14	<10	328	<10	7	160
59	S07-05175	0.8	5.41	10	175	<5	2.94	1	16	261	133	5.00	2.00	10	1.42	678	22	1.16	49	760	36	5	<20	203	0.13	<10	368	<10	5	132
60	S07-05176	0.6	5.89	10	1295	<5	2.10	<1	13	145	103	4.17	1.82	20	1.50	537	16	1.78	41	760	34	<5	<20	190	0.15	<10	310	<10	8	84
61	S07-05177	1.2	6.71	<5	1380	<5	3.22	<1	16	105	92	5.54	2.07	10	2.61	839	<1	2.15	19	750	46	<5	<20	302	0.16	<10	206	<10	6	100
62	S07-05178	0.6	6.88	<5	1365	<5	3.24	<1	16	134	100	5.89	1.88	10	2.60	847	6	2.10	20	840	48	<5	<20	294	0.15	<10	206	<10	7	107
63	S07-05179	0.8	6.07	10	460	<5	3.04	1	18	155	88	5.33	1.81	20	2.15	821	19	1.74	30	860	42	<5	<20	274	0.14	<10	272	<10	6	165
64	S07-05180	1.0	5.44	10	160	<5	2.20	2	13	243	107	4.39	1.93	20	1.38	608	54	0.75	55	960	30	<5	<20	194	0.14	<10	544	<10	6	213
65	S07-05181	0.8	5.81	10	230	<5	2.95	1	26	183	113	5.39	1.90	10	2.02	795	16	1.57	37	800	34	<5	<20	281	0.13	<10	343	<10	6	155
66	S07-05182	0.6	6.39	10	1075	<5	2.91	<1	19	112	77	5.62	1.82	10	2.78	747	<1	2.19	18	800	36	<5	<20	305	0.14	<10	239	<10	6	108
67	S07-05183	0.6	5.36	15	275	<5	2.44	<1	17	186	87	4.01	1.69	20	1.52	632	10	2.08	32	840	26	<5	<20	251	0.13	<10	208	<10	5	66
68	S07-05184	0.4	5.65	10	440	<5	2.56	<1	17	154	105	4.40	1.71	20	1.61	661	10	2.08	36	910	32	<5	<20	249	0.13	<10	201	<10	5	74
69	S07-05185	0.4	4.75	10	395	<5	2.07	<1	11	195	59	3.71	1.55	20	1.42	471	6	1.06	27	600	26	<5	<20	230	0.11	<10	142	<10	7	98
70	S07-05186	0.6	5.00	5	1255	<5	1.74	<1	10	164	48	3.15	1.71	20	1.44	503	7	1.77	20	510	26	<5	<20	206	0.11	<10	118	<10	6	86

I #.	Tag #	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
71	S07-05187	0.8	5.40	15	435	<5	2.22	<1	12	169	68	3.77	1.94	20	1.51	576	10	1.26	23	590	34	<5	<20	252	0.10	<10	137	<10	7	91
72	S07-05188	<0.2	0.08	<5	5	<5	>10	<1	<1	2	<1	0.09	<0.01	<10	1.61	22	<1	0.01	31	50	<2	<5	<20	5714	<0.01	<10	3	<10	<1	1
73	S07-05189	0.4	5.93	<5	1290	<5	2.55	<1	12	259	62	4.38	1.93	20	1.92	544	5	1.19	26	640	26	<5	<20	256	0.10	<10	179	<10	6	104
74	S07-05190	0.2	5.66	5	1225	<5	3.58	<1	10	221	49	3.60	1.52	20	1.92	1063	2	1.90	18	770	22	<5	<20	335	0.09	<10	110	<10	7	71
75	S07-05191	0.2	6.03	15	1710	<5	2.74	<1	10	153	51	3.22	1.74	20	1.67	806	3	1.58	16	720	24	<5	<20	263	0.13	<10	134	<10	7	60
76	S07-05192	0.2	5.20	5	1525	<5	2.13	<1	8	154	48	2.92	1.60	20	1.51	673	7	1.50	17	530	22	<5	<20	205	0.10	<10	113	<10	5	61
77	S07-05193	0.6	5.88	10	840	<5	2.77	<1	15	140	72	3.71	1.78	20	1.56	816	6	1.52	25	640	30	<5	<20	229	0.10	<10	131	<10	7	93
78	S07-05194	0.6	5.85	10	1970	<5	1.61	<1	9	110	73	3.35	1.79	20	1.51	481	14	1.46	23	670	26	<5	<20	181	0.11	<10	163	<10	6	103
79	S07-05195	0.6	6.64	10	180	<5	1.52	<1	16	107	65	4.63	2.55	20	1.39	377	26	0.89	31	720	42	<5	<20	175	0.10	<10	182	<10	7	133
30	S07-05196	0.6	5.64	<5	1700	<5	1.32	1	10	119	82	3.95	1.80	20	1.60	416	8	1.41	31	670	24	<5	<20	163	0.12	<10	213	<10	5	157
31	S07-05197	0.8	5.83	10	700	<5	1.52	2	15	121	88	3.68	2.04	20	1.31	387	18	1.36	41	740	32	<5	<20	180	0.11	<10	269	<10	6	188
32	S07-05198	4.7	4.41	90	320	<5	0.50	2	12	39	600	5.11	2.25	10	1.70	408	7	0.27	23	500	100	50	<20	73	0.30	<10	54	<10	11	671
33	S07-05199	0.6	5.70	<5	1160	<5	2.14	<1	12	98	97	4.15	1.47	20	1.57	630	<1	1.95	28	1030	24	<5	<20	219	0.12	<10	133	<10	5	84
34	S07-05200	0.6	5.45	10	1275	<5	1.52	<1	14	124	84	4.03	1.44	20	1.50	468	2	1.60	30	830	22	<5	<20	203	0.12	<10	141	<10	5	75
35	S07-05201	0.2	4.64	10	730	<5	2.21	<1	10	106	39	3.24	1.31	20	1.36	592	3	1.39	15	470	22	<5	<20	203	0.07	<10	90	<10	5	70
36	S07-05202	<0.2	5.55	10	1130	<5	1.87	<1	10	134	74	3.33	1.89	20	1.39	534	6	1.31	23	560	22	<5	<20	192	0.10	<10	152	<10	6	85
37	S07-05203	0.6	5.56	5	305	<5	1.22	1	14	112	71	4.14	1.97	20	1.40	377	30	1.34	34	660	30	<5	<20	156	0.10	<10	229	<10	6	160
38	S07-05204	0.8	4.78	10	140	<5	2.06	<1	18	141	66	4.49	1.43	20	1.19	526	23	1.21	33	700	26	<5	<20	200	0.10	<10	106	<10	5	73
39	S07-05205	0.6	4.12	5	1365	<5	2.04	<1	11	170	78	3.36	1.21	20	1.39	531	1	1.18	29	740	20	<5	<20	202	0.10	<10	79	<10	6	73
40	S07-05206	0.8	5.20	5	1515	<5	1.60	<1	10	117	81	3.52	1.70	20	1.54	429	200	1.23	31	630	30	<5	<20	194	0.10	<10	168	<10	5	116
41	S07-05207	1.2	5.81	20	640	<5	1.51	2	29	114	82	6.96	2.01	20	1.66	398	19	1.29	44	670	40	<5	<20	159	0.09	<10	201	<10	6	187
42	S07-05208	0.8	6.05	10	1380	<5	1.20	1	11	103	88	3.92	1.62	20	1.51	349	16	1.56	32	790	28	<5	<20	156	0.11	<10	263	<10	6	169
43	S07-05209	0.8	5.82	10	1350	<5	1.11	2	14	107	89	4.08	1.74	20	1.54	336	16	1.52	38	760	30	<5	<20	156	0.12	<10	276	<10	6	192
44	S07-05210	0.8	5.72	10	1250	<5	1.42	<1	18	127	128	4.91	1.73	20	1.67	417	32	1.61	43	980	30	<5	<20	188	0.13	<10	191	<10	6	137
45	S07-05211	1.0	5.50	10	340	<5	1.67	<1	21	140	108	5.20	1.49	20	1.44	436	1	2.02	41	990	26	<5	<20	191	0.14	<10	161	<10	5	107
46	S07-05212	0.8	5.64	20	100	<5	2.40	<1	20	133	85	5.46	1.87	20	1.18	607	<1	1.60	38	830	30	<5	<20	200	0.13	<10	124	<10	5	93
47	S07-05213	0.6	4.55	10	715	<5	2.87	<1	10	135	107	3.13	1.48	20	1.31	826	<1	1.17	28	650	18	<5	<20	208	0.13	<10	104	<10	5	98
48	S07-05214	0.6	5.86	5	1045	<5	3.45	<1	10	121	121	4.01	1.76	20	1.66	875	11	1.60	18	700	26	<5	<20	256	0.14	<10	212	<10	6	111
49	S07-05215	0.6	5.43	10	450	<5	2.56	<1	16	135	93	4.04	1.59	20	1.35	641	45	1.46	32	690	24	<5	<20	221	0.11	<10	210	<10	6	81
50	S07-05216	0.6	5.58	10	230	<5	2.54	1	18	120	94	4.42	1.56	20	1.35	587	8	1.18	28	700	24	<5	<20	215	0.13	<10	209	<10	6	116
51	S07-05217	0.8	4.99	25	375	<5	2.16	<1	11	159	118	3.96	1.48	20	1.28	571	11	1.19	33	690	22	<5	<20	200	0.11	<10	153	<10	6	98
52	S07-05218	1.0	4.64	25	175	<5	2.11	<1	22	144	75	5.64	1.39	20	1.04	529	2	1.15	38	780	28	<5	<20	186	0.10	<10	88	<10	6	91
53	S07-05219	0.6	5.27	15	260	<5	2.21	2	21	153	129	5.10	1.49	20	1.21	520	1	1.20	43	810	26	<5	<20	205	0.11	<10	113	<10	6	186
54	S07-05220	1.6	5.43	15	235	<5	3.36	1	18	165	121	4.56	1.60	20	1.52	756	14	1.00	46	730	26	<5	<20	243	0.11	<10	213	<10	7	131
55	S07-05221	0.6	6.47	15	220	<5	3.34	<1	17	113	91	4.30	1.66	20	1.53	716	16	1.16	33	990	28	<5	<20	243	0.11	<10	193	<10	8	101
56	S07-05222	0.6	5.79	10	300	<5	2.60	1	11	146	88	4.20	1.88	20	1.32	566	19	0.95	27	860	34	<5	<20	190	0.10	<10	199	<10	7	140
57	S07-05223	0.8	5.25	10	525	<5	2.68	1	9	177	73	3.10	1.60	20	1.25	539	16	1.31	34	660	22	<5	<20	209	0.12	<10	251	<10	7	108
58	S07-05224	0.6	5.56	15	200	<5	2.81	1	12	119	80	3.58	1.56	20	1.30	554	9	1.63	34	630	22	<5	<20	208	0.12	<10	235	<10	8	124
59	S07-05225	0.6	5.52	15	210	<5	2.80	1	14	81	74	4.10	1.64	20	1.33	582	9	1.64	39	620	28	<5	<20	205	0.11	<10	226	<10	8	122
10	S07-05226	0.8	5.52	15	155	<5	2.57	1	12	106	62	3.95	1.69	20	1.32	532	11	1.76	41	640	28	<5	<20	210	0.11	<10	274	<10	8	141

I #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
11	S07-05227	0.4	5.51	10	540	<5	3.15	1	8	111	48	3.22	1.65	20	1.49	643	11	1.44	28	680	26	<5	<20	238	0.11	<10	200	<10	7	115
12	S07-05228	0.4	6.27	10	765	<5	3.19	1	7	126	75	2.98	1.75	20	1.43	622	20	1.30	28	1140	26	<5	<20	218	0.12	<10	186	<10	8	111
13	S07-05229	0.2	5.50	10	485	<5	3.47	<1	10	125	103	2.91	1.54	10	1.39	709	6	1.33	19	660	20	<5	<20	258	0.10	<10	136	<10	6	67
14	S07-05230	0.6	4.99	10	495	<5	6.75	<1	11	98	94	3.94	1.56	10	2.83	1946	4	1.36	19	560	22	<5	<20	366	0.06	<10	118	<10	7	57
15	S07-05231	0.4	4.44	10	455	<5	2.95	<1	10	84	70	3.09	1.42	10	1.38	630	7	1.39	22	450	18	<5	<20	197	0.08	<10	149	<10	5	75
16	S07-05232	0.4	4.52	<5	515	<5	2.99	<1	8	105	143	2.86	1.46	10	1.26	566	6	1.12	21	460	16	<5	<20	200	0.09	<10	151	<10	7	66
17	S07-05233	0.4	5.28	10	495	<5	4.14	1	11	103	87	3.75	1.66	20	1.78	785	9	1.35	33	620	24	<5	<20	259	0.10	<10	220	<10	8	112
18	S07-05234	<0.2	0.04	<5	15	<5	>10	<1	<1	1	<1	0.03	<0.01	<10	1.49	15	<1	0.01	31	30	<2	<5	<20	5846	<0.01	<10	1	<10	<1	1
19	S07-05235	0.6	4.84	10	470	<5	3.93	<1	8	98	92	2.67	1.43	10	1.55	779	5	1.15	21	490	18	<5	<20	229	0.09	<10	147	<10	7	53
20	S07-05236	0.8	4.73	10	165	<5	3.17	<1	12	105	65	3.52	1.57	20	1.32	502	13	1.07	27	470	18	<5	<20	231	0.09	<10	174	<10	9	62
21	S07-05237	2.2	5.41	15	220	<5	4.00	2	23	129	84	4.67	1.45	20	1.64	847	9	1.20	44	590	24	<5	<20	259	0.10	<10	212	<10	8	163
22	S07-05238	0.8	4.75	<5	620	<5	1.88	1	11	110	53	3.59	1.76	10	1.31	412	8	1.00	29	500	22	<5	<20	170	0.09	<10	192	<10	6	124
23	S07-05239	0.4	5.36	5	905	<5	2.20	<1	10	94	68	3.60	1.82	20	1.49	455	12	1.36	24	550	26	<5	<20	181	0.10	<10	176	<10	7	120

DATA:

Heat:

2	S07-05118	0.4	6.57	<5	705	<5	3.40	<1	15	39	128	4.63	1.96	20	1.44	863	<1	2.08	6	1050	26	10	<20	517	0.20	<10	143	<10	8	51
0	S07-05126	0.8	6.86	10	710	<5	3.28	<1	16	72	148	5.24	1.69	10	2.11	1133	<1	2.38	23	1000	28	5	<20	569	0.16	<10	226	<10	6	76
9	S07-05135	0.4	6.28	<5	655	<5	3.61	<1	9	45	54	3.29	1.73	20	1.10	748	<1	2.47	8	780	26	<5	<20	687	0.15	<10	91	<10	6	51
6	S07-05152	0.9	5.83	5	1455	<5	2.07	<1	11	58	61	3.83	0.66	20	1.22	592	<1	3.82	11	740	22	<5	<20	417	0.24	<10	133	<10	6	57
5	S07-05161	0.4	7.04	5	440	<5	3.83	<1	21	71	233	6.73	1.08	20	1.69	1032	<1	2.83	11	1790	26	<5	<20	809	0.29	<10	232	<10	12	65
4	S07-05170	0.2	6.74	5	725	<5	3.34	<1	17	116	41	5.30	1.25	10	2.12	1342	<1	2.45	24	670	26	<5	<20	687	0.17	<10	185	<10	4	72
1	S07-05187	0.8	5.90	10	400	<5	2.21	<1	13	168	67	3.95	1.93	20	1.52	631	11	1.25	24	650	38	<5	<20	255	0.10	<10	138	<10	7	103
0	S07-05196	0.5	5.26	5	1665	<5	1.21	1	10	121	81	3.76	1.85	20	1.55	391	8	1.40	29	640	22	<5	<20	156	0.11	<10	214	<10	6	145
9	S07-05205	0.7	4.20	10	1340	<5	2.05	<1	11	172	78	3.45	1.23	20	1.40	543	1	1.23	30	760	20	<5	<20	204	0.11	<10	81	<10	5	71
06	S07-05222	0.9	6.07	10	295	<5	2.64	1	12	145	90	4.38	2.02	20	1.34	588	20	0.96	29	880	36	<5	<20	189	0.10	<10	201	<10	8	149
15	S07-05231	0.4	4.80	5	455	<5	3.11	<1	12	84	70	3.34	1.40	10	1.41	627	8	1.37	24	500	20	<5	<20	204	0.09	<10	153	<10	5	81

plit:


2	S07-05118	0.4	6.53	<5	705	<5	3.43	<1	11	35	131	4.63	1.99	20	1.38	865	<1	2.01	9	1060	24	<5	<20	498	0.21	<10	160	<10	8	54
6	S07-05152	0.8	6.28	<5	1445	<5	2.25	<1	11	61	62	4.12	0.68	20	1.30	611	<1	4.10	12	800	26	<5	<20	423	0.24	<10	133	<10	5	55
1	S07-05187	0.7	5.83	10	455	<5	2.28	<1	13	150	61	3.67	1.82	20	1.49	616	10	1.27	23	620	32	<5	<20	248	0.11	<10	139	<10	8	90
06	S07-05222	0.8	5.55	5	290	<5	2.59	1	13	148	86	3.84	2.12	20	1.43	583	19	1.01	34	820	30	<5	<20	203	0.09	<10	202	<10	8	136


Standard:

D-3		0.4	5.70	20	1355	<5	2.22	<1	15	60	38	4.27	1.45	40	1.31	2474	5	1.21	29	1790	53	5	<20	270	0.33	<10	113	<10	31	208
D-3		0.5	5.46	20	1300	<5	2.27	<1	14	57	36	4.21	1.45	40	1.31	2539	5	1.26	28	1710	54	<5	<20	262	0.31	<10	102	<10	29	196
D-3		0.5	5.66	20	1235	<5	2.32	<1	14	59	36	4.26	1.52	40	1.29	2579	5	1.19	29	1700	52	<5	<20	265	0.31	<10	104	<10	29	199
D-3		0.5	5.86	20	1275	<5	2.33	<1	13	57	35	4.16	1.50	40	1.27	2495	6	1.18	27	1660	50	<5	<20	268	0.29	<10	104	<10	29	209

4 ACID DIGEST/ICP-FINISH

4 ACID DIGEST/AA-FINISH


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2103

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

23-Jan-08


Attention: Bob Singh

No. of samples received: 62
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-142
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-05240	<0.03	<0.001
2	S07-05241	<0.03	<0.001
3	S07-05242	<0.03	<0.001
4	S07-05243	<0.03	<0.001
5	S07-05244	2.05	0.060
6	S07-05245	<0.03	<0.001
7	S07-05246	<0.03	<0.001
8	S07-05248	0.11	0.003
9	S07-05249	<0.03	<0.001
10	S07-05250	<0.03	<0.001
11	S07-05251	<0.03	<0.001
12	S07-05252	<0.03	<0.001
13	S07-05253	0.14	0.004
14	S07-05254	0.49	0.014
15	S07-05255	0.03	0.001
16	S07-05256	0.04	0.001
17	S07-05257	<0.03	<0.001
18	S07-05258	0.11	0.003
19	S07-05259	<0.03	<0.001
20	S07-05260	0.03	0.001
21	S07-05262	<0.03	<0.001
22	S07-05263	<0.03	<0.001
23	S07-05264	<0.03	<0.001
24	S07-05265	0.03	0.001
25	S07-05266	<0.03	<0.001
26	S07-05267	<0.03	<0.001
27	S07-05268	<0.03	<0.001
28	S07-05269	<0.03	<0.001
29	S07-05270	0.03	0.001

* = 30g FA


ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	S07-05271	0.06	0.002
31	S07-05272	0.14	0.004
32	S07-05273	* 0.42	0.012
33	S07-05274	0.12	0.003
34	S07-05275	0.11	0.003
35	S07-05276	0.05	0.001
36	S07-05277	0.04	0.001
37	S07-05278	<0.03	<0.001
38	S07-05279	0.04	0.001
39	S07-05280	0.03	0.001
40	S07-05281	<0.03	<0.001
41	S07-05282	<0.03	<0.001
42	S07-05283	<0.03	<0.001
43	S07-05284	<0.03	<0.001
44	S07-05285	<0.03	<0.001
45	S07-05286	<0.03	<0.001
46	S07-05287	0.04	0.001
47	S07-05288	0.05	0.001
48	S07-05289	<0.03	<0.001
49	S07-05290	<0.03	<0.001
50	S07-05291	<0.03	<0.001
51	S07-05292	<0.03	<0.001
52	S07-05293	<0.03	<0.001
53	S07-05294	<0.03	<0.001
54	S07-05295	<0.03	<0.001
55	S07-05296	0.10	0.003
56	S07-05297	<0.03	<0.001
57	S07-05298	<0.03	<0.001
58	S07-05299	0.03	0.001
59	S07-05300	<0.03	<0.001
60	S07-05301	* <0.03	<0.001
61	S07-05302	<0.03	<0.001
62	S07-05303	<0.03	<0.001

QC DATA:


Resplit:

1	S07-05240	<0.03	<0.001
36	S07-05277	0.04	0.001

Standard:

Ox154	1.82	0.053
Ox154	1.80	0.052

* = 30g FA



ECO TECH LABORATORY LTD.

Julia Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
OX154		1.86	0.054
OX154		1.86	0.054
OX154		1.88	0.055

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nl

XLS/07



ECO TECH LABORATORY LTD.

Jutta Jealouse

B.C. Certified Assayer

CO TECH LABORATORY LTD.

3041 Dallas Drive
AMLOOPS, B.C.
2C 6T4

Phone: 250-573-5700

Fax: 250-573-4557

ICP CERTIFICATE OF ANALYSIS A-007-2103

Skygold Ventures
615 - 800 W. Pender Street
Vancouver, BC
V6B 2V6

No. of samples received: 64

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-142

Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-05240	0.3	7.88	25	1185	<5	3.99	<1	15	125	57	5.60	1.71	20	1.26	1586	<1	1.32	19	1210	40	<5	<20	352	0.26	<10	129	<10	8	113
2	S07-05241	0.5	8.40	75	270	<5	3.40	<1	28	157	85	7.80	2.44	20	1.17	1202	9	0.96	29	1100	46	<5	<20	191	0.25	<10	160	<10	9	128
3	S07-05242	0.6	6.94	30	350	<5	4.45	<1	23	139	112	6.77	1.96	20	1.76	1549	4	1.27	24	1260	38	<5	<20	299	0.23	<10	240	<10	11	123
4	S07-05243	0.5	8.32	25	390	<5	4.90	<1	17	147	74	5.86	1.81	20	1.74	1398	6	1.22	26	1540	50	<5	<20	274	0.28	<10	145	<10	10	138
5	S07-05244	4.8	4.24	245	235	<5	0.58	2	14	41	674	5.16	2.40	10	1.76	463	15	0.29	31	550	110	55	<20	67	0.33	<10	60	<10	13	687
6	S07-05245	0.4	7.72	10	1025	<5	3.57	<1	12	140	63	4.43	1.82	20	1.39	938	<1	1.26	16	850	36	<5	<20	222	0.29	<10	118	<10	9	106
7	S07-05246	0.2	7.64	20	985	<5	3.38	<1	12	99	61	3.40	1.66	20	1.54	703	1	2.19	14	730	40	<5	<20	251	0.19	<10	105	<10	8	107
8	S07-05248	0.6	8.49	30	255	<5	5.07	<1	17	134	78	5.57	2.02	20	1.55	1110	8	1.46	22	1010	48	<5	<20	239	0.26	<10	129	<10	12	92
9	S07-05249	0.3	8.01	15	1030	<5	3.63	<1	17	171	60	5.44	1.57	20	1.72	1182	<1	1.80	21	1030	36	<5	<20	337	0.23	<10	141	<10	7	111
10	S07-05250	0.2	8.35	20	1020	<5	3.72	<1	18	92	44	5.53	1.39	20	1.83	1190	<1	1.66	18	1050	48	<5	<20	399	0.24	<10	135	<10	8	104
11	S07-05251	0.2	7.45	15	890	<5	3.77	<1	18	160	38	5.47	1.21	20	1.69	1258	<1	1.30	17	1140	30	<5	<20	412	0.26	<10	111	<10	8	96
12	S07-05252	<0.2	7.51	20	1015	<5	3.54	<1	15	111	39	5.70	1.27	20	1.88	1198	<1	1.25	15	1180	32	<5	<20	395	0.26	<10	108	<10	8	114
13	S07-05253	0.4	6.94	50	385	<5	4.03	<1	24	164	70	6.35	1.85	20	1.71	1096	<1	0.99	31	1450	30	<5	<20	244	0.22	<10	127	<10	11	84
14	S07-05254	0.4	5.32	95	185	<5	5.76	1	19	206	57	5.97	1.30	10	1.30	1158	59	0.68	62	720	28	<5	<20	225	0.12	<10	249	<10	10	162
15	S07-05255	0.4	6.17	35	445	<5	3.56	<1	10	198	36	2.83	1.83	20	1.56	653	5	1.34	21	420	28	<5	<20	221	0.13	<10	122	<10	9	53
16	S07-05256	0.2	6.79	35	490	<5	4.97	<1	8	112	34	3.25	1.75	20	2.10	908	5	1.31	14	520	26	<5	<20	263	0.12	<10	84	<10	12	69
17	S07-05257	0.6	5.43	20	370	<5	8.20	<1	9	192	34	3.00	1.21	10	1.29	1010	7	0.89	25	940	26	<5	<20	291	0.10	<10	84	<10	11	102
18	S07-05258	0.4	7.03	35	340	<5	3.57	1	11	233	50	3.56	1.43	20	1.52	698	12	0.65	32	680	26	<5	<20	184	0.17	<10	136	<10	10	231
19	S07-05259	<0.2	7.60	5	550	<5	2.93	<1	12	47	39	4.66	0.92	10	1.27	867	6	2.66	31	780	30	<5	<20	308	0.40	<10	116	<10	20	61
20	S07-05260	0.6	7.13	55	335	<5	3.88	<1	19	247	58	3.93	1.10	20	1.29	736	8	1.41	44	1200	28	<5	<20	152	0.19	<10	161	<10	10	88
21	S07-05262	0.4	5.80	55	285	<5	3.53	<1	16	186	103	4.00	1.04	20	1.44	677	2	1.53	28	560	26	<5	<20	172	0.14	<10	99	<10	7	89
22	S07-05263	0.2	7.46	60	545	<5	4.16	<1	14	78	40	3.67	1.40	20	1.80	823	<1	1.56	14	710	28	<5	<20	224	0.15	<10	109	<10	9	50
23	S07-05264	0.3	7.26	70	475	<5	4.24	<1	16	94	69	4.07	0.99	20	2.14	905	3	1.75	15	670	30	<5	<20	249	0.14	<10	100	<10	8	83
24	S07-05265	0.2	7.26	40	675	<5	3.95	<1	12	98	33	3.44	1.26	20	1.96	780	3	1.35	13	550	26	<5	<20	232	0.13	<10	85	<10	10	58
25	S07-05266	0.2	3.91	30	300	<5	4.13	1	11	311	26	3.27	0.84	10	1.00	1045	15	1.01	35	1140	24	<5	<20	149	0.09	<10	102	<10	8	172

Et #.	Tag #	g	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
26	S07-05267	0.4	5.56	40	395	<5	4.63	<1	8	219	62	3.37	0.96	20	1.70	901	<1	1.39	24	460	28	<5	<20	179	0.12	<10	83	<10	8	97
27	S07-05268	0.6	6.69	40	325	<5	3.85	<1	11	172	46	3.37	0.97	30	1.51	800	3	1.56	25	570	28	<5	<20	164	0.15	<10	113	<10	8	93
28	S07-05269	0.4	5.38	35	215	<5	4.92	<1	15	213	53	4.42	1.18	10	1.47	974	12	1.09	39	750	28	<5	<20	188	0.11	<10	138	<10	7	138
29	S07-05270	0.8	5.35	30	325	<5	6.26	<1	16	304	51	3.86	1.02	<10	1.26	1054	8	0.99	43	780	36	<5	<20	229	0.13	<10	145	<10	8	136
30	S07-05271	1.1	5.76	45	240	<5	4.07	1	18	310	67	5.13	1.03	10	1.40	892	12	1.01	38	700	40	5	<20	155	0.13	<10	178	<10	6	154
31	S07-05272	1.4	6.62	35	295	<5	3.25	<1	21	191	83	5.21	1.46	20	1.28	733	17	1.40	40	680	42	<5	<20	139	0.16	<10	206	<10	6	146
32	S07-05273	0.8	5.80	225	290	<5	0.20	<1	9	27	33	3.35	3.79	10	0.28	210	5	0.10	18	490	20	45	<20	43	0.41	<10	75	<10	13	56
33	S07-05274	1.6	7.73	45	120	<5	2.86	<1	25	194	87	5.25	1.64	10	1.17	681	12	2.04	35	740	50	5	<20	140	0.17	<10	235	<10	6	151
34	S07-05275	1.2	6.90	30	370	<5	4.12	<1	23	170	90	5.70	1.41	10	1.40	808	12	1.97	35	860	44	5	<20	172	0.15	<10	188	<10	7	137
35	S07-05276	0.7	6.99	35	375	<5	4.59	<1	30	250	53	4.48	1.26	<10	1.07	715	8	1.44	70	1820	36	<5	<20	216	0.29	<10	205	<10	11	99
36	S07-05277	0.6	7.78	60	205	<5	3.76	<1	32	290	53	4.83	1.63	10	1.26	634	7	1.56	75	2130	36	5	<20	191	0.29	<10	212	<10	11	101
37	S07-05278	0.4	8.37	40	185	<5	3.76	<1	13	162	44	3.72	1.48	20	1.55	570	5	1.46	29	790	34	<5	<20	196	0.16	<10	125	<10	9	77
38	S07-05279	0.4	6.62	30	205	<5	3.18	<1	14	150	63	3.57	1.12	20	1.25	548	12	2.07	31	540	28	<5	<20	188	0.13	<10	128	<10	8	162
39	S07-05280	0.2	6.61	15	405	<5	3.32	<1	10	144	45	3.18	1.00	20	1.29	505	10	2.29	26	560	24	<5	<20	198	0.14	<10	137	<10	7	123
40	S07-05281	0.4	6.24	70	300	<5	3.56	<1	14	179	42	3.83	0.81	20	1.36	571	11	1.97	33	590	22	<5	<20	199	0.13	<10	126	<10	8	124
41	S07-05282	0.4	6.63	35	300	<5	4.23	<1	14	179	40	4.10	0.91	10	1.62	638	9	2.02	37	730	24	<5	<20	223	0.15	<10	127	<10	9	153
42	S07-05283	0.6	9.35	65	115	<5	3.44	<1	38	246	55	5.52	2.17	10	1.30	485	3	2.05	87	2930	42	<5	<20	216	0.32	<10	239	<10	11	110
43	S07-05284	0.4	8.62	70	140	<5	2.97	<1	35	256	57	5.31	2.12	10	1.29	443	3	1.90	79	2260	34	<5	<20	200	0.28	<10	239	<10	10	111
44	S07-05285	0.4	7.39	30	320	<5	3.73	1	18	179	46	4.18	0.94	20	1.47	592	9	2.07	49	1560	32	<5	<20	229	0.23	<10	155	<10	10	224
45	S07-05286	0.3	5.82	25	255	<5	2.73	<1	14	202	31	3.82	0.79	20	1.11	508	11	2.41	30	520	24	<5	<20	190	0.11	<10	110	<10	7	112
46	S07-05287	<0.2	5.51	15	495	<5	4.02	<1	6	165	80	2.78	0.88	20	1.65	793	9	1.65	19	640	24	<5	<20	246	0.10	<10	83	<10	8	80
47	S07-05288	0.2	5.86	15	555	<5	3.79	<1	8	161	49	3.22	0.91	20	1.63	559	1	1.64	18	470	24	<5	<20	224	0.16	<10	86	<10	10	54
48	S07-05289	0.4	5.12	30	345	<5	3.13	<1	13	210	68	3.27	0.75	20	1.45	627	2	1.97	27	400	22	<5	<20	217	0.14	<10	83	<10	7	70
49	S07-05290	0.6	8.16	35	285	<5	3.72	<1	17	144	127	3.88	1.10	20	1.67	726	<1	2.01	19	730	30	<5	<20	257	0.20	<10	145	<10	6	92
50	S07-05291	0.8	8.29	40	240	<5	4.10	<1	21	159	121	4.75	1.27	20	1.81	806	<1	1.93	23	780	30	<5	<20	266	0.21	<10	150	<10	7	96
51	S07-05292	0.4	7.65	30	615	<5	3.80	<1	14	62	76	3.80	1.13	20	1.92	803	<1	1.70	15	670	26	<5	<20	283	0.15	<10	125	<10	7	57
52	S07-05293	0.2	7.39	35	870	<5	3.73	<1	10	109	70	3.64	1.06	20	2.01	793	<1	1.53	13	670	30	<5	<20	279	0.17	<10	102	<10	9	71
53	S07-05294	0.4	7.64	30	1055	<5	4.13	<1	13	127	63	3.48	1.19	20	2.20	953	2	1.54	13	670	28	<5	<20	278	0.17	<10	107	<10	10	71
54	S07-05295	0.4	7.75	45	910	<5	3.26	<1	13	139	58	3.29	1.19	20	1.72	721	<1	1.37	15	590	28	<5	<20	236	0.18	<10	102	<10	9	70
55	S07-05296	0.2	6.84	40	545	<5	3.75	<1	12	219	54	3.22	1.02	20	1.52	867	3	1.32	17	660	26	<5	<20	231	0.18	<10	98	<10	10	81
56	S07-05297	<0.2	7.13	20	1370	<5	4.35	<1	7	153	61	2.77	1.22	20	1.69	976	2	1.07	14	490	24	<5	<20	211	0.19	<10	90	<10	14	63
57	S07-05298	0.2	5.67	50	210	<5	2.05	<1	11	257	52	3.08	1.37	10	0.84	567	6	1.13	15	500	24	<5	<20	131	0.16	<10	94	<10	6	58
58	S07-05299	<0.2	7.20	35	440	<5	3.06	<1	8	134	46	2.96	2.12	20	1.32	752	<1	0.89	9	450	24	<5	<20	177	0.19	<10	61	<10	9	70
59	S07-05300	0.2	7.89	45	360	<5	4.02	<1	16	94	94	4.22	1.08	20	1.57	887	8	1.76	17	810	32	<5	<20	237	0.23	<10	151	<10	9	121
60	S07-05301	<0.2	0.88	<5	100	<5	>10	<1	<1	1	<1	0.12	0.06	<10	1.59	63	<1	0.03	27	60	18	<5	<20	4789	<0.01	<10	1	<10	<1	3
61	S07-05302	0.4	6.04	40	425	<5	8.56	<1	11	152	73	3.58	1.26	10	0.99	1522	9	1.48	19	670	30	<5	<20	404	0.12	<10	82	<10	13	111
62	S07-05303	0.6	7.31	35	905	<5	4.11	<1	13	160	80	4.10	1.63	20	1.58	920	10	1.36	16	750	30	<5	<20	254	0.21	<10	140	<10	8	79

C DATA:


Repeat:

1	S07-05240	0.4	8.14	30	1220	<5	4.14	<1	16	133	60	6.06	1.80	20	1.32	1623	<1	1.39	21	1250	40	<5	<20	357	0.27	<10	136	<10	10	117
10	S07-05250	0.2	8.22	15	1025	<5	3.54	<1	16	93	44	5.49	1.07	20	1.85	1206	<1	1.55	17	1030	42	<5	<20	401	0.27	<10	135	<10	10	95
20	S07-05260	1.0	6.96	55	325	<5	3.89	<1	19	248	61	3.92	1.63	10	1.29	744	9	1.32	45	1190	34	<5	<20	152	0.19	<10	163	<10	10	88
36	S07-05277	0.6	7.92	50	215	<5	3.50	<1	31	268	53	5.00	1.63	20	1.26	619	7	1.63	74	2140	34	<5	<20	191	0.29	<10	222	<10	11	96
45	S07-05286	0.3	5.81	35	255	<5	2.95	<1	14	210	31	3.75	0.75	20	1.14	505	11	2.45	31	510	22	<5	<20	189	0.11	<10	108	<10	7	108


Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
Split:																														
1	S07-05240	0.3	7.78	20	1110	<5	3.84	<1	16	122	50	5.48	1.47	20	1.23	1512	<1	1.36	17	1170	36	<5	<20	374	0.28	<10	140	<10	9	107
36	S07-05277	0.6	7.40	65	215	<5	3.81	<1	32	275	52	4.73	1.40	10	1.18	590	7	1.65	73	2070	38	<5	<20	178	0.23	<10	204	<10	8	98
Standard:																														
sd3		0.5	5.71	30	1325	<5	2.58	<1	18	66	46	4.47	1.26	40	1.35	2597	8	1.16	36	1710	64	<5	<20	266	0.37	<10	121	<10	32	207
sd3		0.5	5.86	25	1380	<5	2.51	<1	17	61	42	4.21	1.39	30	1.29	2559	7	1.11	32	1680	58	<5	<20	267	0.35	<10	120	<10	32	198

P: 4 ACID DIGEST/ICP-FINISH
 G: 4 ACID DIGEST/AA-FINISH

l/nl
 td2103S
 .S/07



ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2291

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

12-Mar-08


Attention: Bob Singh

No. of samples received: 139
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-143
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-05304	<0.03	<0.001
2	S07-05305	<0.03	<0.001
3	S07-05306	<0.03	<0.001
4	S07-05307	<0.03	<0.001
5	S07-05308	<0.03	<0.001
6	S07-05309	<0.03	<0.001
7	S07-05310	<0.03	<0.001
8	S07-05311	<0.03	<0.001
9	S07-05312	<0.03	<0.001
10	S07-05313	2.02	0.059
11	S07-05314	<0.03	<0.001
12	S07-05315	<0.03	<0.001
13	S07-05316	0.03	0.001
14	S07-05317	<0.03	<0.001
15	S07-05318	<0.03	<0.001
16	S07-05319	<0.03	<0.001
17	S07-05320	<0.03	<0.001
18	S07-05321	<0.03	<0.001
19	S07-05322	<0.03	<0.001
20	S07-05323	<0.03	<0.001
21	S07-05324	<0.03	<0.001
22	S07-05325	<0.03	<0.001
23	S07-05326	<0.03	<0.001
24	S07-05327	<0.03	<0.001
25	S07-05328	<0.03	<0.001
26	S07-05329	0.61	0.018
27	S07-05330	<0.03	<0.001


* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
28	S07-05331	<0.03	<0.001
29	S07-05332	<0.03	<0.001
30	S07-05333	<0.03	<0.001
31	S07-05334	<0.03	<0.001
32	S07-05335	<0.03	<0.001
33	S07-05336	<0.03	<0.001
34	S07-05337	<0.03	<0.001
35	S07-05338	<0.03	<0.001
36	S07-05339	<0.03	<0.001
37	S07-05340	<0.03	<0.001
38	S07-05341	<0.03	<0.001
39	S07-05342	<0.03	<0.001
40	S07-05343	<0.03	<0.001
41	S07-05344	0.13	0.004
42	S07-05345	0.45	0.013
43	S07-05346	0.43	0.013
44	S07-05347	<0.03	<0.001
45	S07-05348	0.06	0.002
46	S07-05349	0.47	0.014
47	S07-05350	0.25	0.007
48	S07-05351	0.12	0.004
49	S07-05352	<0.03	<0.001
50	S07-05353	0.06	0.002
51	S07-05354	<0.03	<0.001
52	S07-05355	<0.03	<0.001
53	S07-05356	<0.03	<0.001
54	S07-05357	<0.03	<0.001
55	S07-05358	<0.03	<0.001
56	S07-05359	<0.03	<0.001
57	S07-05360	<0.03	<0.001
58	S07-05361	<0.03	<0.001
59	S07-05362	0.03	0.001
60	S07-05363	<0.03	<0.001
61	S07-05364	0.06	0.002
62	S07-05365	<0.03	<0.001
63	S07-05366	0.03	0.001
64	S07-05367	<0.03	<0.001
65	S07-05368	0.04	0.001
66	S07-05369	0.03	0.001
67	S07-05370	<0.03	<0.001
68	S07-05371	<0.03	<0.001
69	S07-05372	<0.03	<0.001
70	S07-05373	<0.03	<0.001

* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
71	S07-05374	<0.03	<0.001
72	S07-05375	<0.03	<0.001
73	S07-05376	<0.03	<0.001
74	S07-05377	0.05	0.001
75	S07-05378	0.30	0.009
76	S07-05379	1.86	0.054
77	S07-05380	0.04	0.001
78	S07-05381	<0.03	<0.001
79	S07-05382	2.09	0.061
80	S07-05383	<0.03	<0.001
81	S07-05384	0.11	0.003
82	S07-05385	0.04	0.001
83	S07-05386	0.10	0.003
84	S07-05387	0.44	0.013
85	S07-05388	<0.03	<0.001
86	S07-05389	0.10	0.003
87	S07-05390	<0.03	<0.001
88	S07-05391	<0.03	<0.001
89	S07-05392	0.03	0.001
90	S07-05393	<0.03	<0.001
91	S07-05394	<0.03	<0.001
92	S07-05395	0.04	0.001
93	S07-05396	0.09	0.003
94	S07-05397	3.02	0.088
95	S07-05398	<0.03	<0.001
96	S07-05399	1.60	0.047
97	S07-05400	1.36	0.040
98	S07-05401	0.07	0.002
99	S07-05402	0.12	0.004
100	S07-05403	0.36	0.010
101	S07-05404	0.30	0.009
102	S07-05405	0.35	0.010
103	S07-05406	0.62	0.018
104	S07-05407	0.38	0.011
105	S07-05408	0.03	0.001
106	S07-05409	0.04	0.001
107	S07-05410	0.14	0.004
108	S07-05411	0.05	0.002
109	S07-05412	<0.03	<0.001
110	S07-05413	0.03	0.001
111	S07-05414	0.06	0.002
112	S07-05415	0.42	0.012
113	S07-05416	<0.03	<0.001

* = 30g FA

Jutta Jealouse
ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
114	S07-05417	<0.03	<0.001
115	S07-05418	<0.03	<0.001
116	S07-05419	<0.03	<0.001
117	S07-05420	<0.03	<0.001
118	S07-05421	<0.03	<0.001
119	S07-05422	<0.03	<0.001
120	S07-05423	<0.03	<0.001
121	S07-05424	<0.03	<0.001
122	S07-05425	<0.03	<0.001
123	S07-05426	<0.03	<0.001
124	S07-05427	<0.03	<0.001
125	S07-05428	0.15	0.004
126	S07-05429	0.11	0.003
127	S07-05430	0.25	0.007
128	S07-05431	0.21	0.006
129	S07-05432	<0.03	<0.001
130	S07-05433	<0.03	<0.001
131	S07-05434	<0.03	<0.001
132	S07-05435	<0.03	<0.001
133	S07-05436	0.03	0.001
134	S07-05437	<0.03	<0.001
135	S07-05438	0.05	0.001
136	S07-05439	0.06	0.002
137	S07-05440	0.06	0.002
138	S07-05441	0.13	0.004
139	S07-05442	0.14	0.004

QC DATA:**Resplit:**

1	S07-05304	<0.03	<0.001
36	S07-05339	<0.03	<0.001
71	S07-05374	<0.03	<0.001
106	S07-05409	0.09	0.003

Standard:

OXI54	1.90	0.055
OXI54	1.90	0.055
OXI54	1.86	0.054
OXI54	1.84	0.054
OXI54	1.84	0.054
OXI54	1.90	0.055
OXI54	1.90	0.055
OXI54	1.80	0.052
OXI54	1.90	0.055
OXI54	1.88	0.055

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw
XLS/07

Janice B. Jones
ECO TECH LABORATORY LTD.
 Jutta Sealouse
 B.C. Certified Assayer

CO TECH LABORATORY LTD.

0041 Dallas Drive

AMLOOPS, B.C.

2C 6T4

Phone: 250-573-5700

Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AN 2007- 2291

Skygold Ventures

615 - 800 W. Pender Street

Vancouver, BC

V6B 2V6

No. of samples received: 139

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-143

Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-05304	<0.2	7.56	10	440	<5	3.98	<1	13	91	66	4.13	2.24	20	1.61	829	10	1.66	15	880	38	<5	<20	296	0.16	<10	140	<10	8	69
2	S07-05305	<0.2	6.45	10	365	<5	3.54	<1	9	119	35	3.43	1.86	20	1.52	796	3	0.73	13	680	28	<5	<20	321	0.13	<10	91	<10	9	74
3	S07-05306	<0.2	6.82	5	270	<5	5.83	<1	15	92	72	4.92	2.08	10	2.10	1590	1	1.09	15	1180	32	<5	<20	398	0.15	<10	137	<10	9	98
4	S07-05307	0.2	7.76	5	375	<5	3.92	<1	16	68	68	4.56	2.33	20	1.89	1116	2	0.85	17	1190	38	<5	<20	362	0.19	<10	136	<10	8	122
5	S07-05308	0.4	7.27	10	390	<5	3.12	<1	17	91	65	4.42	2.25	20	1.68	871	2	0.72	19	1100	34	<5	<20	328	0.17	<10	128	<10	8	115
6	S07-05309	<0.2	7.75	<5	1185	<5	3.37	<1	10	76	44	4.17	2.43	20	1.98	1002	<1	0.96	12	1520	32	<5	<20	328	0.16	<10	85	<10	9	83
7	S07-05310	<0.2	7.37	<5	800	<5	2.97	<1	14	90	36	4.87	1.82	20	2.29	1130	<1	1.24	14	1420	34	<5	<20	524	0.17	<10	105	<10	7	105
8	S07-05311	<0.2	7.32	5	880	<5	3.70	<1	14	73	40	4.48	1.90	20	2.08	1106	<1	1.45	15	820	32	<5	<20	479	0.15	<10	128	<10	5	83
9	S07-05312	<0.2	6.87	<5	790	<5	3.49	<1	13	85	34	3.94	1.57	<10	1.61	1092	<1	1.41	13	680	26	<5	<20	526	0.15	<10	127	<10	4	72
10	S07-05313	4.5	4.50	95	305	<5	0.50	1	11	35	627	5.03	2.47	10	1.68	377	7	0.27	24	510	102	45	<20	71	0.27	<10	51	<10	11	667
11	S07-05314	<0.2	7.84	<5	950	<5	3.61	<1	15	54	43	4.62	1.87	10	1.98	1081	<1	1.59	14	920	36	<5	<20	520	0.13	<10	145	<10	5	84
12	S07-05315	<0.2	7.23	<5	450	<5	5.01	<1	16	78	75	4.70	1.87	20	2.03	1261	<1	1.42	14	1130	32	<5	<20	501	0.14	<10	130	<10	7	98
13	S07-05316	0.2	7.81	5	465	<5	3.95	<1	20	86	110	5.99	2.08	10	1.75	1088	5	1.32	20	1000	36	<5	<20	471	0.14	<10	160	<10	6	85
14	S07-05317	<0.2	7.48	5	960	<5	2.91	<1	18	78	62	4.56	1.83	10	1.82	1064	2	1.41	25	690	28	<5	<20	545	0.15	<10	165	<10	4	88
15	S07-05318	<0.2	7.19	<5	885	<5	3.23	<1	20	96	54	4.66	1.63	20	1.89	1184	<1	1.47	24	920	32	<5	<20	478	0.13	<10	131	<10	5	79
16	S07-05319	<0.2	7.47	<5	685	<5	3.31	<1	18	77	82	4.41	1.33	10	1.83	1135	<1	1.49	24	950	30	<5	<20	640	0.13	<10	153	<10	4	72
17	S07-05320	<0.2	7.42	5	220	<5	4.18	<1	20	90	91	4.56	0.51	10	2.61	1054	<1	2.50	29	690	26	<5	<20	650	0.14	<10	163	<10	5	60
18	S07-05321	<0.2	7.47	10	510	<5	4.25	<1	14	83	74	4.04	0.83	10	1.75	947	<1	2.34	21	720	32	<5	<20	708	0.13	<10	127	<10	5	59
19	S07-05322	<0.2	7.81	<5	730	<5	4.87	<1	13	98	69	4.32	1.20	10	1.96	1035	<1	1.93	18	900	32	<5	<20	684	0.13	<10	135	<10	4	56
20	S07-05323	<0.2	8.08	5	1135	<5	4.58	<1	16	66	56	4.53	0.86	<10	2.24	1104	<1	2.29	20	940	30	<5	<20	795	0.11	<10	171	<10	3	68
21	S07-05324	<0.2	8.91	10	395	<5	5.38	<1	20	92	69	5.08	0.79	<10	2.33	1431	<1	2.41	21	990	34	<5	<20	1098	0.11	<10	198	<10	4	64
22	S07-05325	0.2	8.19	5	205	<5	5.49	<1	18	40	231	6.28	0.48	10	2.20	1483	<1	2.77	13	1850	32	<5	<20	828	0.18	<10	208	<10	10	78
23	S07-05326	0.2	8.12	<5	205	<5	5.43	<1	16	29	213	6.25	0.49	10	2.18	1494	<1	2.69	14	1820	34	<5	<20	839	0.19	<10	210	<10	10	76
24	S07-05327	<0.2	7.27	5	150	<5	7.02	<1	18	106	241	5.36	0.40	10	2.17	1642	<1	2.81	15	1420	32	<5	<20	746	0.25	<10	191	<10	9	53
25	S07-05328	<0.2	8.07	<5	155	<5	6.27	<1	19	53	274	5.52	0.40	10	2.20	1547	<1	3.05	14	1540	30	<5	<20	744	0.24	<10	201	<10	10	59

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La mg%	Mn	Mo Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
26	S07-05329	<0.2	6.29	<5	100	<5	6.17	<1	17	81	190	6.14	0.30	10 2.11 1528	<1	2.20	13 1830	28	<5	<20	643	0.20	<10	178	<10	11	61	
27	S07-05330	<0.2	6.80	5	110	<5	4.77	<1	22	52	219	6.16	0.35	20 2.47 1412	2	2.56	12 2060	26	<5	<20	511	0.24	<10	206	<10	13	79	
28	S07-05331	<0.2	6.89	<5	135	<5	5.29	<1	19	63	189	5.88	0.36	20 2.08 1303	1	2.74	13 1850	28	<5	<20	504	0.22	<10	178	<10	13	71	
29	S07-05332	0.2	7.44	10	180	<5	4.37	<1	20	56	208	6.24	0.48	10 2.15 1242	<1	2.71	13 2070	32	<5	<20	504	0.21	<10	195	<10	12	64	
30	S07-05333	<0.2	7.64	10	120	<5	4.54	<1	21	56	203	6.54	0.36	10 2.15 1337	<1	2.90	13 2140	32	<5	<20	451	0.23	<10	198	<10	13	77	
31	S07-05334	<0.2	7.06	5	125	<5	3.70	<1	16	78	136	5.24	0.33	20 2.16 1079	<1	2.68	13 1510	26	<5	<20	490	0.21	<10	157	<10	12	62	
32	S07-05335	<0.2	6.97	5	180	<5	3.96	<1	13	102	90	4.17	0.38	10 1.85 889	<1	2.37	15 820	28	<5	<20	658	0.14	<10	135	<10	6	40	
33	S07-05336	<0.2	0.11	<5	10	<5	>10	<1	<1	<1	3	0.04	<0.01	<10 1.89 16	<1	0.01	26 50	4	<5	<20	5826	<0.01	<10	2	<10	<1	3	
34	S07-05337	<0.2	6.87	<5	170	<5	3.88	<1	14	90	87	4.30	0.37	20 1.85 1202	<1	2.24	12 1240	28	<5	<20	774	0.15	<10	128	<10	7	43	
35	S07-05338	<0.2	7.22	5	125	<5	3.30	<1	13	108	82	4.59	0.29	20 1.82 1088	<1	3.10	13 1440	26	<5	<20	524	0.20	<10	139	<10	11	44	
36	S07-05339	<0.2	7.40	5	175	<5	2.98	<1	15	81	43	4.20	0.38	10 1.81 879	<1	3.28	18 830	28	<5	<20	506	0.20	<10	157	<10	4	66	
37	S07-05340	<0.2	7.48	<5	435	<5	6.25	<1	11	47	32	4.13	0.77	20 1.94 1327	<1	2.29	10 1140	30	<5	<20	758	0.14	<10	90	<10	8	80	
38	S07-05341	<0.2	7.79	5	885	<5	4.79	<1	15	56	60	4.37	1.49	<10 2.04 1239	<1	1.81	16 920	28	<5	<20	538	0.16	<10	148	<10	5	68	
39	S07-05342	0.2	7.77	<5	1135	<5	4.05	<1	14	55	63	4.17	1.84	10 2.00 885	<1	1.96	14 730	28	<5	<20	464	0.14	<10	136	<10	4	66	
40	S07-05343	0.2	8.20	5	1125	<5	3.46	<1	16	71	84	4.31	1.79	<10 1.83 973	<1	2.54	14 740	36	<5	<20	422	0.15	<10	147	<10	4	70	
41	S07-05344	0.4	7.07	10	355	<5	5.18	<1	14	80	109	4.47	2.42	10 2.17 1076	10	1.04	45 760	40	<5	<20	357	0.12	<10	171	<10	5	87	
42	S07-05345	0.6	5.51	20	350	<5	3.62	1	11	148	108	3.23	2.06	10 1.46 920	9	0.49	55 890	32	<5	<20	216	0.10	<10	141	<10	6	134	
43	S07-05346	0.8	5.73	105	245	<5	0.23	<1	7	27	33	3.52	4.25	10 0.33 157	3	0.10	15 480	22	35	<20	50	0.36	<10	65	<10	10	46	
44	S07-05347	0.2	4.08	15	890	<5	3.34	<1	7	205	46	2.06	1.52	10 1.43 804	1	0.41	50 360	24	<5	<20	216	0.09	<10	72	<10	5	81	
45	S07-05348	0.2	4.83	25	1035	<5	3.45	<1	7	173	58	2.25	1.80	20 1.47 795	<1	0.50	68 410	22	<5	<20	221	0.11	<10	72	<10	6	96	
46	S07-05349	0.2	4.03	10	320	<5	2.74	<1	8	264	56	2.32	1.51	10 1.16 671	5	0.31	59 310	26	<5	<20	198	0.08	<10	114	<10	6	65	
47	S07-05350	1.2	6.08	15	290	<5	3.64	2	18	196	107	4.48	2.14	10 1.60 767	20	0.98	47 920	34	<5	<20	237	0.10	<10	315	<10	6	199	
48	S07-05351	0.6	6.69	5	240	<5	3.34	2	14	269	111	4.26	2.20	20 1.51 694	21	1.19	46 900	30	<5	<20	238	0.11	<10	322	<10	6	198	
49	S07-05352	<0.2	7.00	<5	1145	<5	3.17	<1	10	191	62	3.05	2.17	20 1.59 624	10	1.55	25 660	30	<5	<20	269	0.10	<10	182	<10	7	88	
50	S07-05353	0.2	6.33	5	290	<5	3.42	<1	14	197	79	3.85	1.81	20 1.81 880	10	1.39	33 790	34	<5	<20	302	0.10	<10	205	<10	6	123	
51	S07-05354	0.4	7.82	10	1130	<5	2.83	<1	20	123	96	4.65	1.95	10 2.30 817	<1	2.04	24 910	42	<5	<20	289	0.17	<10	188	<10	5	107	
52	S07-05355	0.6	6.59	15	250	<5	2.88	<1	12	171	65	3.70	1.86	20 1.54 776	11	1.54	34 680	34	<5	<20	237	0.16	<10	205	<10	7	81	
53	S07-05356	0.2	6.41	5	1315	<5	2.61	<1	8	141	69	2.36	1.92	20 1.41 670	11	1.47	19 580	26	<5	<20	218	0.11	<10	119	<10	6	89	
54	S07-05357	0.2	5.76	10	1150	<5	2.28	<1	8	121	42	2.36	1.60	10 1.34 604	4	1.47	20 550	26	<5	<20	192	0.11	<10	125	<10	5	88	
55	S07-05358	0.2	6.24	10	470	<5	1.74	1	13	119	79	3.43	1.82	20 1.43 473	15	1.56	38 720	34	<5	<20	157	0.10	<10	223	<10	5	173	
56	S07-05359	0.6	5.48	10	250	<5	2.59	<1	14	200	99	3.34	1.49	20 1.35 670	2	1.27	36 740	32	<5	<20	206	0.10	<10	149	<10	6	99	
57	S07-05360	0.2	5.63	5	415	<5	2.63	<1	12	205	101	3.20	1.51	20 1.41 704	2	1.29	36 750	28	<5	<20	214	0.12	<10	148	<10	5	103	
58	S07-05361	0.6	7.35	10	485	<5	3.15	<1	17	125	101	4.58	1.88	20 1.93 737	9	1.89	28 820	34	<5	<20	249	0.16	<10	211	<10	6	113	
59	S07-05362	0.4	6.65	10	415	<5	3.67	<1	23	112	75	4.80	1.58	10 2.34 901	30	1.71	31 860	44	<5	<20	259	0.13	<10	210	<10	6	131	
60	S07-05363	0.2	8.06	<5	1295	<5	3.65	<1	19	80	88	5.16	1.86	10 2.79 873	<1	2.06	19 870	46	<5	<20	286	0.14	<10	201	<10	5	141	
61	S07-05364	0.8	6.32	15	330	<5	3.19	2	25	168	72	5.01	2.00	10 1.54 753	68	1.02	77 1010	36	<5	<20	202	0.14	<10	545	<10	6	251	
62	S07-05365	0.4	6.84	15	1285	<5	4.57	2	10	158	91	3.72	1.94	20 1.80 1149	48	1.39	49 1070	34	<5	<20	269	0.15	<10	468	<10	6	280	
63	S07-05366	0.3	5.29	20	245	<5	3.48	2	17	294	74	4.36	1.62	20 1.32 790	79	0.87	76 1000	36	<5	<20	200	0.12	<10	408	<10	5	219	
64	S07-05367	0.4	7.87	5	1310	<5	4.20	<1	16	126	85	4.63	1.82	10 2.34 955	1	1.98	23 950	36	<5	<20	293	0.15	<10	219	<10	5	134	
65	S07-05368	0.4	5.99	10	975	<5	2.51	<1	12	228	95	3.39	1.42	20 1.49 587	6	1.67	33 780	30	<5	<20	207	0.16	<10	182	<10	5	102	

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
66	S07-05369	0.4	5.27	25	135	<5	2.98	<1	15	198	70	3.74	1.29	20	1.20	729	5	1.32	38	840	34	<5	<20	207	0.14	<10	148	<10	5	73
67	S07-05370	<0.2	0.10	<5	20	<5	>10	<1	<1	<1	<1	0.04	<0.01	<10	1.78	21	<1	0.01	24	40	<2	<5	<20	5996	<0.01	<10	2	<10	<1	2
68	S07-05371	0.2	5.48	10	280	<5	3.14	<1	9	142	64	3.27	1.29	20	1.47	767	2	1.42	22	660	26	<5	<20	224	0.15	<10	153	<10	6	45
69	S07-05372	0.4	7.38	5	975	<5	3.71	<1	17	93	77	4.71	1.67	10	2.45	913	2	1.78	25	940	38	<5	<20	282	0.20	<10	215	<10	6	106
70	S07-05373	<0.2	7.49	5	1070	<5	2.99	<1	19	64	50	5.44	1.40	10	3.17	939	<1	2.33	18	850	42	<5	<20	258	0.20	<10	193	<10	5	149
71	S07-05374	0.2	7.39	<5	1185	<5	2.97	<1	22	75	68	5.60	1.52	10	3.07	1015	1	2.22	23	890	42	<5	<20	286	0.18	<10	202	<10	6	141
72	S07-05375	<0.2	5.44	10	330	<5	3.02	<1	14	166	72	3.74	1.32	20	1.34	848	2	1.47	30	970	24	<5	<20	248	0.16	<10	133	<10	7	55
73	S07-05376	<0.2	5.66	10	270	<5	2.39	<1	16	141	75	3.73	1.46	20	1.31	740	2	1.31	36	900	28	<5	<20	200	0.17	<10	158	<10	7	80
74	S07-05377	<0.2	6.74	<5	1435	<5	3.22	<1	14	131	88	4.25	1.69	20	1.92	1235	<1	1.53	35	970	32	<5	<20	253	0.18	<10	128	<10	7	113
75	S07-05378	<0.2	6.56	10	425	<5	2.77	<1	16	142	64	4.08	1.90	20	1.70	1229	3	1.07	38	870	34	<5	<20	222	0.15	<10	143	<10	7	91
76	S07-05379	1.2	6.25	10	460	<5	2.86	1	20	166	75	4.06	2.15	10	1.61	1521	8	0.73	42	630	100	<5	<20	200	0.11	<10	142	<10	6	139
77	S07-05380	0.8	4.82	15	900	<5	1.76	<1	24	138	69	3.87	1.52	20	1.42	2384	<1	0.53	63	410	34	<5	<20	152	0.14	<10	63	<10	5	93
78	S07-05381	0.4	4.29	20	1010	<5	1.45	<1	25	82	45	3.22	1.36	20	1.25	2774	<1	0.47	58	340	24	<5	<20	150	0.15	<10	66	<10	5	78
79	S07-05382	4.8	4.40	90	255	<5	0.50	1	11	34	622	4.93	2.61	10	1.70	372	7	0.26	23	490	102	45	<20	72	0.26	<10	52	<10	11	658
80	S07-05383	0.4	4.06	15	1910	<5	1.35	<1	21	109	67	3.09	1.32	20	1.27	2428	<1	0.39	54	310	26	<5	<20	128	0.15	<10	48	<10	5	79
81	S07-05384	0.6	3.49	15	1490	<5	1.47	<1	15	138	78	2.59	1.15	20	1.07	1993	<1	0.32	49	280	20	<5	<20	120	0.12	<10	47	<10	4	66
82	S07-05385	0.2	2.59	10	325	<5	2.11	<1	12	193	60	2.31	0.84	10	0.91	1979	<1	0.25	36	170	16	<5	<20	125	0.07	<10	49	<10	4	32
83	S07-05386	0.8	2.28	5	200	<5	2.56	<1	14	132	116	3.61	0.72	20	0.98	2474	<1	0.24	54	250	22	<5	<20	153	0.05	<10	56	<10	6	32
84	S07-05387	0.6	2.00	5	195	<5	2.32	<1	13	126	98	3.18	0.50	20	0.89	2473	<1	0.27	56	220	18	<5	<20	166	0.06	<10	48	<10	5	30
85	S07-05388	0.8	3.64	10	375	<5	1.81	<1	16	125	135	4.14	0.75	30	1.26	2981	<1	0.82	98	320	32	<5	<20	202	0.10	<10	57	<10	8	60
86	S07-05389	0.8	2.01	10	320	<5	1.45	<1	14	171	88	3.34	0.41	20	0.94	3246	<1	0.38	56	260	24	<5	<20	154	0.07	<10	44	<10	6	55
87	S07-05390	0.4	2.97	15	730	<5	1.67	<1	15	161	90	3.45	0.70	20	1.22	2891	<1	0.49	69	300	22	<5	<20	163	0.08	<10	52	<10	5	58
88	S07-05391	0.4	3.58	30	1085	<5	1.84	<1	18	141	86	3.17	0.91	30	1.25	2853	<1	0.66	63	1390	18	<5	<20	189	0.11	<10	59	<10	8	57
89	S07-05392	0.4	2.43	15	365	<5	1.91	<1	17	149	80	3.09	0.54	20	1.04	2914	<1	0.46	63	280	16	<5	<20	176	0.09	<10	44	<10	5	43
90	S07-05393	0.4	2.77	10	785	<5	1.75	<1	12	85	84	2.79	0.72	20	1.30	3101	<1	0.51	45	520	22	<5	<20	173	0.08	<10	44	<10	5	63
91	S07-05394	0.4	2.60	15	675	<5	1.79	<1	12	95	66	2.57	0.68	20	1.10	2583	<1	0.42	43	360	20	<5	<20	157	0.08	<10	41	<10	4	59
92	S07-05395	0.6	5.57	10	255	<5	3.46	<1	27	116	139	4.33	1.51	20	1.74	2193	<1	0.77	73	510	30	<5	<20	229	0.15	<10	95	<10	7	76
93	S07-05396	0.6	4.69	5	350	<5	1.87	<1	12	152	100	3.27	1.72	20	1.01	1243	10	0.39	53	700	30	<5	<20	121	0.12	<10	188	<10	6	88
94	S07-05397	1.2	5.62	10	405	<5	2.26	<1	24	162	119	5.34	2.06	20	0.89	1093	25	0.48	84	2460	30	<5	<20	131	0.12	<10	237	<10	9	87
95	S07-05398	<0.2	0.15	<5	35	<5	>10	<1	<1	1	1	0.11	0.01	<10	1.91	25	<1	0.05	19	50	<2	<5	<20	6035	0.01	<10	6	<10	<1	7
96	S07-05399	1.6	4.87	10	405	<5	1.74	<1	24	204	95	5.17	1.81	20	0.74	709	27	0.37	81	950	24	<5	<20	104	0.10	<10	226	<10	6	44
97	S07-05400	0.6	5.48	15	370	<5	1.92	<1	27	242	133	4.90	1.99	20	0.92	824	24	0.46	74	1420	22	<5	<20	124	0.11	<10	236	<10	8	48
98	S07-05401	0.2	5.93	5	380	<5	3.44	<1	9	100	62	3.15	2.19	10	1.52	934	8	0.49	27	520	20	<5	<20	202	0.10	<10	147	<10	9	55
99	S07-05402	0.4	6.46	5	360	<5	2.52	1	13	95	68	3.88	2.28	20	1.48	748	19	0.95	34	640	26	<5	<20	179	0.10	<10	219	<10	7	141
100	S07-05403	0.4	5.91	15	220	<5	2.23	2	16	117	98	3.88	2.06	20	1.40	798	13	1.03	49	670	26	<5	<20	174	0.11	<10	260	<10	6	180
101	S07-05404	0.8	6.60	10	155	<5	2.78	1	14	112	78	3.52	2.28	20	1.48	853	13	1.22	47	740	28	<5	<20	200	0.12	<10	283	<10	8	124
102	S07-05405	0.4	6.54	10	460	<5	2.78	<1	16	116	80	3.96	2.27	20	1.49	858	13	1.24	47	720	26	<5	<20	199	0.12	<10	278	<10	8	112
103	S07-05406	0.4	6.24	5	280	<5	2.56	2	19	125	63	4.28	2.04	20	1.54	713	14	1.05	48	690	26	<5	<20	175	0.10	<10	253	<10	7	198
104	S07-05407	0.4	6.02	10	385	<5	2.36	2	28	146	67	4.51	2.00	10	1.44	533	14	0.76	54	690	32	<5	<20	162	0.09	<10	232	<10	6	194
105	S07-05408	0.6	5.39	15	330	<5	2.67	1	13	160	67	3.16	1.65	10	1.39	517	10	0.74	34	610	36	<5	<20	185	0.10	<10	189	<10	7	128

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
106	S07-05409	0.8	5.77	15	160	<5	2.07	1	15	98	75	4.40	1.52	10	1.55	495	7	1.36	35	600	40	<5	<20	163	0.10	<10	184	<10	6	138
107	S07-05410	0.6	6.28	15	475	<5	2.00	2	21	194	76	4.33	1.82	10	1.28	444	17	1.29	69	1010	34	<5	<20	162	0.11	<10	247	<10	6	175
108	S07-05411	0.6	6.38	15	150	<5	2.78	1	23	218	89	4.24	1.89	10	1.40	564	19	1.33	66	1400	36	<5	<20	179	0.11	<10	223	<10	6	152
109	S07-05412	0.4	7.10	10	410	<5	3.71	<1	14	100	79	3.60	1.96	10	1.87	858	7	1.52	26	1020	42	<5	<20	258	0.10	<10	139	<10	6	86
110	S07-05413	0.4	7.13	15	255	<5	3.62	<1	15	130	61	4.10	1.89	10	2.23	746	2	1.58	23	970	38	<5	<20	255	0.10	<10	137	<10	7	101
111	S07-05414	0.2	8.13	10	675	<5	3.49	1	17	160	82	4.17	2.24	10	2.02	701	6	1.58	45	1660	36	<5	<20	237	0.14	<10	188	<10	7	143
112	S07-05415	0.8	5.44	105	325	<5	0.24	<1	8	24	31	3.37	4.24	10	0.30	171	3	0.12	15	510	24	40	<20	52	0.37	<10	68	<10	11	49
113	S07-05416	0.2	7.77	5	630	<5	4.11	<1	11	140	68	3.46	2.15	10	2.01	790	5	1.74	34	2450	32	<5	<20	269	0.11	<10	162	<10	9	95
114	S07-05417	0.4	7.66	5	1135	<5	2.78	<1	22	104	80	4.42	1.78	10	2.52	633	1	2.03	25	830	40	<5	<20	243	0.10	<10	131	<10	6	102
115	S07-05418	0.4	7.49	<5	1335	<5	2.21	<1	10	86	46	3.63	1.66	10	2.27	594	<1	2.32	18	720	34	<5	<20	226	0.10	<10	140	<10	5	67
116	S07-05419	0.4	7.20	5	1050	<5	3.01	<1	11	75	50	3.82	1.39	20	2.37	813	<1	2.56	18	1040	32	<5	<20	256	0.10	<10	134	<10	7	85
117	S07-05420	0.4	7.36	5	1145	<5	1.94	<1	11	72	48	3.94	1.40	10	2.50	618	<1	2.60	18	830	32	<5	<20	220	0.11	<10	139	<10	6	88
118	S07-05421	0.2	7.47	5	1085	<5	2.29	<1	11	74	45	3.95	1.37	10	2.44	665	1	2.44	18	810	32	<5	<20	229	0.10	<10	138	<10	6	106
119	S07-05422	0.2	7.44	<5	1115	<5	2.23	<1	11	47	49	3.67	1.44	10	2.41	643	1	2.63	17	830	28	<5	<20	230	0.12	<10	145	<10	6	73
120	S07-05423	0.4	7.27	5	965	<5	1.51	<1	13	79	44	4.20	1.33	10	2.62	475	<1	2.50	18	730	24	<5	<20	197	0.09	<10	132	<10	5	102
121	S07-05424	0.2	7.54	5	975	<5	1.43	<1	14	90	42	4.28	1.31	10	2.65	471	1	2.67	20	730	26	<5	<20	192	0.12	<10	142	<10	5	122
122	S07-05425	<0.2	6.85	10	310	<5	2.67	<1	13	109	48	3.82	1.35	10	1.99	801	1	2.36	18	860	26	<5	<20	228	0.09	<10	130	<10	5	70
123	S07-05426	0.2	7.65	10	705	<5	3.14	<1	15	110	45	4.08	1.60	10	2.11	753	2	2.44	23	880	30	<5	<20	256	0.10	<10	143	<10	6	81
124	S07-05427	0.4	8.10	10	425	<5	3.66	<1	19	186	54	4.16	1.74	10	1.94	829	2	2.74	57	1640	36	<5	<20	288	0.14	<10	172	<10	8	100
125	S07-05428	0.6	7.62	15	150	<5	3.89	<1	25	221	101	4.05	1.65	10	1.57	923	11	2.52	67	1790	34	<5	<20	273	0.15	<10	188	<10	8	113
126	S07-05429	0.6	6.78	20	145	<5	3.21	1	17	163	54	4.14	1.68	10	1.18	874	21	1.82	47	1750	48	<5	<20	201	0.11	<10	183	<10	7	138
127	S07-05430	0.8	6.26	10	170	<5	2.58	1	17	216	89	4.13	1.70	10	1.06	709	26	1.55	55	1380	38	<5	<20	171	0.11	<10	243	<10	7	130
128	S07-05431	0.4	6.16	10	70	<5	2.93	1	17	164	91	4.48	1.64	10	1.22	823	23	1.66	52	1340	42	<5	<20	191	0.10	<10	234	<10	7	142
129	S07-05432	0.4	8.10	25	390	<5	5.28	<1	47	453	58	5.84	1.07	<10	4.18	1698	<1	2.98	138	580	44	<5	<20	458	0.14	<10	173	<10	6	132
130	S07-05433	0.4	7.18	30	385	<5	5.62	<1	38	451	55	5.19	0.87	<10	3.91	1915	<1	2.59	137	480	38	<5	<20	477	0.12	<10	157	<10	6	89
131	S07-05434	0.2	7.59	30	290	<5	3.46	<1	39	429	45	5.80	1.00	<10	4.40	1172	<1	2.68	145	560	30	<5	<20	393	0.15	<10	180	<10	4	129
132	S07-05435	0.2	6.95	35	380	<5	4.03	<1	29	400	46	5.21	1.06	<10	3.50	1688	4	2.25	113	630	30	<5	<20	404	0.13	<10	171	<10	6	95
133	S07-05436	1.2	6.22	30	315	<5	3.43	2	22	160	80	4.59	1.92	10	1.51	1202	26	0.74	76	1240	30	<5	<20	268	0.11	<10	257	<10	8	185
134	S07-05437	0.6	5.62	10	175	<5	4.31	<1	10	201	80	3.19	1.17	10	1.59	1340	13	1.83	34	720	20	<5	<20	276	0.10	<10	154	<10	7	103
135	S07-05438	0.6	6.67	20	95	<5	4.00	<1	23	181	33	3.84	1.71	10	1.26	869	11	1.95	69	6330	34	<5	<20	314	0.17	<10	201	<10	18	98
136	S07-05439	0.6	7.24	40	230	<5	6.82	<1	30	287	147	4.51	1.55	<10	2.80	1748	8	1.92	119	1050	36	<5	<20	466	0.10	<10	158	<10	7	68
137	S07-05440	1.2	5.10	25	115	<5	5.31	2	24	169	90	4.63	1.61	10	2.14	1380	20	0.57	103	940	38	<5	<20	294	0.07	<10	213	<10	6	196
138	S07-05441	1.8	4.57	15	165	<5	3.50	3	18	131	69	4.49	1.63	20	1.41	950	25	0.26	77	1190	54	10	<20	180	0.06	<10	219	<10	6	261
139	S07-05442	2.2	4.63	20	105	<5	4.34	2	17	152	64	4.68	1.57	20	1.80	1188	25	0.28	82	1000	60	10	<20	221	0.07	<10	219	<10	6	235

DATA:


Repeat:


1	S07-05304	0.2	8.26	10	410	<5	4.06	<1	13	93	70	4.30	2.41	20	1.67	866	10	1.82	15	910	34	<5	<20	307	0.14	<10	141	<10	8	69
11	S07-05314	<0.2	7.74	<5	930	<5	3.76	<1	15	51	42	4.36	1.81	10	1.94	1073	<1	1.60	15	920	30	<5	<20	510	0.14	<10	143	<10	5	85
19	S07-05322	<0.2	7.96	5	740	<5	5.06	<1	14	99	69	4.23	1.19	10	1.99	1054	<1	2.00	18	940	30	<5	<20	692	0.13	<10	136	<10	4	56
36	S07-05339	<0.2	7.38	10	175	<5	2.80	<1	16	81	45	4.20	0.39	10	1.80	884	<1	3.35	17	830	30	<5	<20	508	0.20	<10	154	<10	6	66
45	S07-05348	0.2	4.83	25	1040	<5	3.49	<1	8	173	60	2.20	1.79	20	1.48	793	<1	0.49	67	410	26	<5	<20	226	0.12	<10	73	<10	7	93
54	S07-05357	<0.2	6.00	10	1200	<5	2.41	<1	8	131	44	2.57	1.68	10	1.42	629	5	1.56	23	570	26	<5	<20	200	0.11	<10	135	<10	6	94
71	S07-05374	0.2	7.17	<5	1105	<5	2.91	<1	21	65	62	5.11	1.39	10	2.87	942	<1	2.11	21	830	40	<5	<20	266	0.16	<10	184	<10	6	131
80	S07-05383	0.4	3.90	10	1870	<5	1.29	<1	21	112	66	2.90	1.27	20	1.24	2373	<1	0.38	49	300	22	<5	<20	127	0.14	<10	45	<10	5	81

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
89	S07-05392	0.6	2.45	10	305	<5	1.95	<1	14	152	78	3.12	0.57	20	1.07	2873	<1	0.49	59	270	16	<5	<20	180	0.09	<10	46	<10	5	44
106	S07-05409	0.8	5.63	10	160	<5	2.05	1	13	94	73	4.17	1.51	20	1.52	481	6	1.34	34	590	40	<5	<20	159	0.10	<10	179	<10	6	133
115	S07-05418	0.4	7.33	<5	1305	<5	1.18	<1	11	85	46	3.60	1.61	<10	2.20	591	<1	2.33	19	710	34	<5	<20	219	0.11	<10	138	<10	5	71
124	S07-05427	0.4	7.87	15	465	<5	3.68	<1	17	175	52	4.21	1.71	10	1.91	810	3	2.62	53	1630	32	<5	<20	283	0.16	<10	173	<10	9	99
Resplit:																														
1	S07-05304	<0.2	7.88	10	465	<5	4.08	<1	14	81	66	4.22	2.37	20	1.76	897	11	1.79	14	920	34	<5	<20	314	0.14	<10	143	<10	9	70
36	S07-05339	<0.2	7.24	5	175	<5	3.00	<1	17	71	45	4.16	0.40	10	1.86	881	<1	3.44	17	830	26	<5	<20	508	0.24	<10	168	<10	4	66
71	S07-05374	0.3	7.22	5	1110	<5	3.10	<1	21	78	62	5.50	1.41	10	2.97	956	1	2.02	21	810	40	<5	<20	264	0.17	<10	188	<10	6	137
106	S07-05409	0.6	5.92	15	155	<5	2.13	1	15	93	80	4.42	1.58	20	1.53	496	7	1.33	36	630	42	<5	<20	161	0.11	<10	199	<10	6	145
Standard:																														
Stsd3		0.5	5.61	20	1240	<5	2.68	<1	15	59	36	3.99	1.43	30	1.31	2504	5	1.16	33	1690	58	<5	<20	246	0.32	<10	103	<10	27	199
Stsd3		0.4	5.62	25	1295	<5	2.67	<1	16	63	37	4.12	1.41	40	1.24	2604	5	1.17	35	1690	56	<5	<20	260	0.35	<10	117	<10	29	205
Stsd3		0.4	5.72	25	1230	<5	2.60	<1	15	58	37	3.94	1.42	30	1.36	2513	5	1.18	32	1690	50	<5	<20	251	0.32	<10	103	<10	27	207
Stsd3		0.4	5.81	20	1255	<5	2.63	<1	15	60	34	4.04	1.42	30	1.31	2590	5	1.17	32	1710	52	<5	<20	263	0.33	<10	119	<10	28	207

IP: 4 ACID DIGEST/ICP-FINISH
 G: 4 ACID DIGEST/AA-FINISH

l/nw
 td2291s
 .S/07


 ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 1968

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

8-Jan-08

Attention: Bob Singh

No. of samples received: 53
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-144
Submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-34072	<0.03	<0.001
2	S07-34073	<0.03	<0.001
3	S07-34074	<0.03	<0.001
4	S07-34075	<0.03	<0.001
5	S07-34076	<0.03	<0.001
6	S07-34077	* <0.03	<0.001
7	S07-34078	<0.03	<0.001
8	S07-34079	<0.03	<0.001
9	S07-34080	0.04	0.001
10	S07-34081	<0.03	<0.001
11	S07-34083	0.03	0.001
12	S07-34084	0.07	0.002
13	S07-34085	0.14	0.004
14	S07-34087	0.09	0.003
15	S07-34088	0.03	0.001
16	S07-34089	* 0.44	0.013
17	S07-34090	0.07	0.002
18	S07-34091	0.25	0.007
19	S07-34092	0.03	0.001
20	S07-34093	0.03	0.001
21	S07-34094	<0.03	<0.001
22	S07-34095	<0.03	<0.001
23	S07-34096	0.04	0.001
24	S07-34097	0.05	0.001
25	S07-34098	<0.03	<0.001

* = 30g FA

ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	S07-34099	<0.03	<0.001
27	S07-34100	<0.03	<0.001
28	S07-34101	<0.03	<0.001
29	S07-34102	<0.03	<0.001
30	S07-34103	0.03	0.001
31	S07-34104	<0.03	<0.001
32	S07-34105	<0.03	<0.001
33	S07-34106	<0.03	<0.001
34	S07-34107	<0.03	<0.001
35	S07-34108	<0.03	<0.001
36	S07-34109	<0.03	<0.001
37	S07-34110	<0.03	<0.001
38	S07-34111	<0.03	<0.001
39	S07-34112	<0.03	<0.001
40	S07-34113	<0.03	<0.001
41	S07-34114	<0.03	<0.001
42	S07-34115	<0.03	<0.001
43	S07-34116	<0.03	<0.001
44	S07-34117	<0.03	<0.001
45	S07-34118	<0.03	<0.001
46	S07-34119	<0.03	<0.001
47	S07-34120	<0.03	<0.001
48	S07-34121	<0.03	<0.001
49	S07-34122	<0.03	<0.001
50	S07-34123	<0.03	<0.001
51	S07-34124	<0.03	<0.001
52	S07-34125	<0.03	<0.001
53	S07-34126	<0.03	<0.001

QC DATA:

Resplit:

1	S07-34072	<0.03	<0.001
36	S07-34109	<0.03	<0.001


Standard:

OXi54	1.84	0.054
OXi54	1.86	0.054
OXi54	1.82	0.053
OXi54	1.88	0.055

* = 30g FA

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

J/sa
XLS/07


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

CO TECH LABORATORY LTD.

1041 Dallas Drive
AMLOOPS, B.C.
PO BOX 674

Phone: 250-573-5700

Fax: 250-573-4557

ICP CERTIFICATE OF ANALYSIS ANALYSIS 07-1968

Skygold Ventures
615 - 800 W. Pender Street
Vancouver, BC
V6B 2V6

No. of samples received: 53

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-144

Submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-34072	0.3	7.29	30	1005	<5	2.00	<1	14	63	90	3.99	1.33	20	0.53	1003	4	1.55	20	970	34	<5	<20	255	0.19	<10	134	<10	9	118
2	S07-34073	0.2	7.49	25	1020	15	3.20	<1	15	141	59	4.40	1.36	20	0.39	1271	2	1.29	17	780	32	<5	<20	312	0.19	<10	135	<10	8	99
3	S07-34074	0.2	8.16	20	1370	10	3.17	<1	13	119	65	4.91	1.61	20	0.35	1094	7	1.32	18	980	42	<5	<20	320	0.20	<10	145	<10	10	122
4	S07-34075	<0.2	7.73	15	1335	10	4.03	<1	14	101	82	5.28	1.58	20	0.82	1349	1	1.10	13	1280	36	<5	<20	385	0.21	<10	116	<10	11	112
5	S07-34076	0.4	8.27	30	1400	10	4.77	<1	14	141	100	4.90	1.74	20	1.58	1375	10	0.86	20	1100	38	<5	<20	224	0.26	<10	153	<10	12	90
6	S07-34077	<0.2	7.26	10	590	<5	2.75	<1	11	47	41	4.12	0.95	10	1.30	791	4	2.39	27	710	28	5	<20	290	0.38	<10	110	<10	21	59
7	S07-34078	0.6	6.26	25	1105	10	3.97	<1	15	126	114	4.43	1.56	20	1.48	1329	8	1.05	19	1000	36	<5	<20	222	0.19	<10	167	<10	10	100
8	S07-34079	0.4	7.85	10	1475	10	3.50	<1	16	121	74	5.21	1.77	20	1.66	1066	6	1.33	16	1070	40	5	<20	245	0.28	<10	138	<10	11	172
9	S07-34080	0.4	6.74	20	1240	<5	3.41	<1	11	112	78	3.92	1.94	20	1.56	866	1	1.22	13	810	32	<5	<20	215	0.24	<10	111	<10	12	126
10	S07-34081	0.4	6.85	35	935	10	4.65	<1	13	128	63	4.03	1.49	10	2.29	809	3	1.45	15	660	32	<5	<20	267	0.14	<10	118	<10	10	86
11	S07-34083	0.4	6.47	15	995	10	4.21	<1	10	107	85	3.75	1.31	20	1.44	971	9	1.29	15	970	32	5	<20	322	0.17	<10	107	<10	9	117
12	S07-34084	0.7	7.25	25	1350	10	3.46	<1	15	44	107	5.80	1.78	20	1.93	1152	<1	1.17	16	1070	40	<5	<20	212	0.18	<10	133	<10	8	182
13	S07-34085	0.4	6.52	20	960	<5	4.19	<1	9	117	75	3.76	1.61	10	1.44	959	1	1.29	13	860	28	<5	<20	210	0.19	<10	117	<10	10	71
14	S07-34087	<0.2	5.93	20	640	10	4.87	<1	10	124	37	3.25	1.06	20	2.02	983	<1	1.75	10	610	26	<5	<20	281	0.09	<10	62	<10	9	65
15	S07-34088	0.5	7.48	30	620	5	4.36	<1	12	117	59	3.71	1.75	10	1.78	651	3	1.28	15	540	36	<5	<20	228	0.13	<10	115	<10	12	101
16	S07-34089	0.7	5.91	195	505	<5	0.23	3	8	27	37	3.38	4.22	10	0.31	183	3	0.10	15	450	26	40	<20	43	0.39	<10	76	<10	13	52
17	S07-34090	0.8	6.69	20	690	10	3.82	1	11	152	80	3.37	1.55	20	1.56	618	4	1.30	22	550	32	5	<20	170	0.14	<10	121	<10	8	128
18	S07-34091	0.2	6.53	50	570	15	3.85	1	16	195	90	3.68	1.36	20	1.65	695	2	1.82	33	730	26	<5	<20	230	0.18	<10	123	<10	7	78
19	S07-34092	<0.2	6.88	20	1125	<5	2.99	<1	8	101	41	2.71	1.57	20	1.72	535	2	1.58	10	490	30	<5	<20	217	0.13	<10	80	<10	8	65
20	S07-34093	0.3	6.51	30	1080	10	3.54	<1	11	88	49	3.02	1.54	20	1.92	658	1	1.58	11	580	30	<5	<20	250	0.12	<10	96	<10	7	72
21	S07-34094	<0.2	6.32	15	1255	<5	2.14	<1	7	74	31	2.21	1.58	20	1.43	427	2	1.48	8	460	28	<5	<20	188	0.12	<10	72	<10	7	65
22	S07-34095	0.2	6.95	25	950	10	4.55	<1	8	111	42	2.92	1.31	20	2.12	1021	2	1.69	10	580	30	<5	<20	269	0.13	<10	72	<10	10	68
23	S07-34096	<0.2	6.80	55	625	5	4.89	1	13	62	52	3.62	1.53	20	2.33	1105	<1	1.47	12	640	28	<5	<20	280	0.13	<10	95	<10	7	63
24	S07-34097	0.4	5.29	45	475	15	3.09	1	10	233	75	3.59	1.10	20	1.21	541	11	1.18	28	510	22	5	<20	151	0.13	<10	89	<10	8	139
25	S07-34098	<0.2	5.03	70	425	10	2.88	2	14	223	52	3.49	0.91	20	1.10	605	7	1.38	48	540	28	5	<20	128	0.15	<10	101	<10	5	132
26	S07-34099	0.4	6.34	45	810	5	6.52	1	9	173	47	2.89	1.23	20	1.31	1126	4	1.56	22	660	26	5	<20	265	0.12	<10	89	<10	9	101
27	S07-34100	<0.2	6.13	15	1215	5	3.74	<1	5	105	87	2.13	1.54	10	1.51	795	3	1.45	11	460	24	<5	<20	164	0.13	<10	91	<10	7	74
28	S07-34101	<0.2	6.13	20	960	<5	4.04	<1	10	161	72	3.12	1.48	20	1.21	833	7	1.46	14	570	28	5	<20	191	0.15	<10	107	<10	8	74
29	S07-34102	0.2	6.13	45	555	5	3.57	<1	11	145	57	3.21	1.41	10	1.08	841	4	1.69	13	710	26	<5	<20	183	0.15	<10	89	<10	7	65
30	S07-34103	0.6	7.04	30	645	<5	3.78	<1	12	127	77	4.06	1.72	20	1.46	906	3	1.57	13	820	32	5	<20	194	0.23	<10	111	<10	9	103

Et #.	Tag #	g	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
31	S07-34104	0.3	7.15	20	1445	10	3.30	<1	11	118	73	3.66	1.78	20	1.46	877	3	1.21	14	880	28	5	<20	175	0.22	<10	93	<10	10	129
32	S07-34105	0.6	6.67	30	540	10	3.22	<1	13	122	63	4.10	1.92	20	1.48	875	4	1.23	15	770	26	<5	<20	173	0.19	<10	89	<10	9	128
33	S07-34106	<0.2	6.61	15	1200	10	5.68	<1	9	57	58	3.30	1.50	20	1.29	1253	3	1.67	11	710	28	<5	<20	263	0.18	<10	86	<10	11	77
34	S07-34107	0.4	7.43	20	575	<5	4.07	<1	15	103	98	5.02	1.84	20	1.55	1010	<1	1.14	18	1140	32	<5	<20	213	0.24	<10	150	<10	9	135
35	S07-34108	0.6	7.44	25	790	10	3.50	<1	18	111	89	4.98	1.83	20	1.86	1010	<1	1.08	19	950	32	<5	<20	225	0.20	<10	159	<10	8	133
36	S07-34109	<0.2	6.80	10	1135	<5	2.79	<1	17	107	65	4.90	1.71	10	1.99	1035	3	1.12	16	960	30	<5	<20	208	0.22	<10	130	<10	6	117
37	S07-34110	<0.2	7.79	20	1135	<5	4.44	<1	17	72	84	4.91	1.68	20	2.28	1614	1	0.93	14	1380	34	<5	<20	336	0.24	<10	114	<10	10	128
38	S07-34111	<0.2	7.51	10	1135	15	3.50	<1	13	96	64	4.92	1.62	20	2.19	1304	2	0.90	13	1210	34	<5	<20	293	0.23	<10	112	<10	8	125
39	S07-34112	<0.2	7.54	5	900	5	3.01	<1	14	56	31	5.03	1.39	20	2.14	1138	<1	1.02	11	990	36	<5	<20	397	0.21	<10	106	<10	6	133
40	S07-34113	<0.2	6.95	20	1040	<5	3.59	<1	17	183	60	5.17	1.62	10	1.88	1187	1	0.86	18	940	30	5	<20	309	0.21	<10	167	<10	8	118
41	S07-34114	<0.2	8.08	<5	1055	20	4.99	<1	18	82	72	5.38	1.57	10	2.21	1541	<1	1.17	14	1070	34	<5	<20	402	0.22	<10	172	<10	8	143
42	S07-34115	0.2	7.55	15	735	10	4.12	<1	21	59	102	5.53	1.49	20	1.77	1239	<1	0.99	18	1310	34	5	<20	367	0.16	<10	160	<10	6	127
43	S07-34116	<0.2	7.21	5	855	5	3.13	<1	20	130	89	5.21	1.66	10	1.69	999	3	0.89	23	760	32	<5	<20	313	0.19	<10	193	<10	5	103
44	S07-34117	<0.2	7.32	<5	975	<5	3.27	<1	14	106	53	4.26	1.52	10	1.49	976	1	0.93	19	620	32	<5	<20	381	0.22	<10	120	<10	5	103
45	S07-34118	0.2	7.07	5	1025	5	3.32	<1	7	115	74	3.53	1.59	20	1.10	927	2	1.03	10	650	32	<5	<20	439	0.16	<10	60	<10	7	90
46	S07-34119	<0.2	1.26	<5	90	<5	>10	<1	<1	8	1	0.17	0.07	<10	1.91	60	<1	0.03	41	70	4	<5	<20	4997	<0.01	<10	3	<10	1	4
47	S07-34120	<0.2	7.21	5	1000	<5	2.69	<1	15	79	73	4.29	1.53	20	1.48	945	4	1.18	16	780	32	<5	<20	390	0.19	<10	118	<10	6	118
48	S07-34121	<0.2	7.77	<5	800	5	3.50	<1	14	79	73	4.34	1.37	20	1.67	1188	1	1.34	16	1180	32	<5	<20	526	0.21	<10	164	<10	6	116
49	S07-34122	<0.2	7.42	10	740	15	2.80	<1	23	91	79	5.01	1.27	20	1.50	1092	<1	1.27	26	860	34	<5	<20	443	0.18	<10	129	<10	6	104
50	S07-34123	<0.2	8.89	<5	1015	10	4.04	<1	21	83	165	5.85	1.59	10	1.97	1733	<1	1.40	24	810	38	<5	<20	590	0.22	<10	225	<10	4	157
51	S07-34124	<0.2	7.95	<5	1055	10	3.56	<1	21	96	50	5.03	1.53	20	1.79	1091	4	0.95	21	870	34	<5	<20	464	0.20	<10	143	<10	6	108
52	S07-34125	<0.2	7.80	<5	980	15	3.11	<1	13	75	49	4.52	1.54	20	1.78	1123	<1	1.35	15	920	34	<5	<20	481	0.20	<10	140	<10	5	110
53	S07-34126	<0.2	7.38	20	610	<5	4.68	<1	23	157	59	5.45	0.89	10	2.48	1493	<1	1.38	37	680	30	<5	<20	625	0.21	<10	165	<10	6	86

DATA:**Repeat:**

1	S07-34072	0.3	7.84	35	1020	5	2.03	<1	14	61	96	4.35	1.44	20	0.51	998	4	1.79	19	1020	34	<5	<20	261	0.18	<10	141	<10	8	123
10	S07-34081	0.4	6.86	30	925	15	4.55	<1	12	131	62	4.03	1.46	10	2.34	825	3	1.41	16	660	30	<5	<20	271	0.14	<10	117	<10	10	90
19	S07-34092	<0.2	6.89	20	1125	5	2.97	<1	8	97	41	2.67	1.57	10	1.69	529	2	1.58	9	470	28	<5	<20	216	0.12	<10	78	<10	7	62
36	S07-34109	<0.2	6.96	20	1080	15	2.85	<1	16	105	61	4.97	1.75	10	2.01	1063	2	1.10	17	950	28	5	<20	209	0.21	<10	127	<10	7	113

Split:


1	S07-34072	0.3	7.83	25	975	5	2.18	<1	13	70	93	4.25	1.32	20	0.70	1056	4	1.60	18	990	36	<5	<20	272	0.17	<10	141	<10	8	123
36	S07-34109	<0.2	6.92	10	1175	<5	2.90	<1	15	94	59	4.97	1.60	10	2.01	1084	3	1.10	14	1020	32	<5	<20	210	0.23	<10	131	<10	6	111

Standard:

SD 3		0.5	5.77	20	1340	<5	2.49	1	17	62	44	4.37	1.41	40	1.36	2511	6	1.15	33	1740	60	5	<20	263	0.36	<10	124	<10	35	210
SD 3		0.5	5.80	25	1325	<5	2.50	1	17	63	42	4.23	1.39	40	1.31	2575	6	1.14	32	1670	56	<5	<20	269	0.35	<10	122	<10	32	208

p: 4 ACID DIGEST/ICP-FINISH

i: 4 ACID DIGEST/AA-FINISH



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 1997

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

2-Jan-08

Attention: Bob Singh


No. of samples received: 123
Sample Type: Rock
Project: Spanish Mountain
Shipment #: SMC-07-146
Submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-34127	<0.03	<0.001
2	S07-34128	<0.03	<0.001
3	S07-34129	<0.03	<0.001
4	S07-34130	<0.03	<0.001
5	S07-34131	<0.03	<0.001
6	S07-34132	<0.03	<0.001
7	S07-34133	<0.03	<0.001
8	S07-34134	* 2.04	0.059
9	S07-34135	<0.03	<0.001
10	S07-34136	<0.03	<0.001
11	S07-34137	<0.03	<0.001
12	S07-34138	<0.03	<0.001
13	S07-34139	0.04	0.001
14	S07-34140	<0.03	<0.001
15	S07-34141	<0.03	<0.001
16	S07-34142	<0.03	<0.001
17	S07-34143	<0.03	<0.001
18	S07-34144	0.04	0.001
19	S07-34145	0.03	0.001
20	S07-34146	0.04	0.001
21	S07-34147	<0.03	<0.001
22	S07-34148	0.51	0.015
23	S07-34149	<0.03	<0.001
24	S07-34150	* <0.03	<0.001
25	S07-34151	<0.03	<0.001

* = 30g FA


ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer



Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	S07-34152	0.03	0.001
27	S07-34153	0.05	0.001
28	S07-34154	0.49	0.014
29	S07-34155	0.04	0.001
30	S07-34156	<0.03	<0.001
31	S07-34157	0.04	0.001
32	S07-34158	* 6.76	0.197
33	S07-34159	0.03	0.001
34	S07-34160	0.04	0.001
35	S07-34161	0.04	0.001
36	S07-34162	0.06	0.002
37	S07-34163	0.15	0.004
38	S07-34164	0.16	0.005
39	S07-34165	<0.03	<0.001
40	S07-34166	0.07	0.002
41	S07-34167	0.05	0.001
42	S07-34168	0.31	0.009
43	S07-34169	0.34	0.010
44	S07-34170	0.35	0.010
45	S07-34171	0.22	0.007
46	S07-34172	0.45	0.013
47	S07-34173	0.17	0.005
48	S07-34174	0.04	0.001
49	S07-34175	0.08	0.002
50	S07-34176	0.06	0.002
51	S07-34177	<0.03	<0.001
52	S07-34178	<0.03	<0.001
53	S07-34179	<0.03	<0.001
54	S07-34180	<0.03	<0.001
55	S07-34181	<0.03	<0.001
56	S07-34182	0.03	0.001
57	S07-34183	<0.03	<0.001
58	S07-34184	0.08	0.002
59	S07-34185	* 0.44	0.013
60	S07-34186	0.09	0.003
61	S07-34187	0.11	0.003
62	S07-34188	0.08	0.002
63	S07-34189	0.07	0.002
64	S07-34190	<0.03	<0.001
65	S07-34191	0.07	0.002
66	S07-34192	0.06	0.002
67	S07-34193	0.03	0.001
68	S07-34194	* <0.03	<0.001
69	S07-34195	0.09	0.003
70	S07-34196	0.08	0.002


* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
71	S07-34197	0.13	0.004
72	S07-34198	0.10	0.003
73	S07-34199	<0.03	<0.001
74	S07-34200	0.30	0.009
75	S07-34201	0.10	0.003
76	S07-34202	0.13	0.004
77	S07-34203	0.39	0.011
78	S07-34204	0.13	0.004
79	S07-34205	0.13	0.004
80	S07-34206	0.14	0.004
81	S07-34207	0.13	0.004
82	S07-34208	0.11	0.003
83	S07-34209	0.05	0.001
84	S07-34210	0.03	0.001
85	S07-34211	0.05	0.001
86	S07-34212	0.09	0.003
87	S07-34213	0.04	0.001
88	S07-34214	0.13	0.004
89	S07-34215	0.14	0.004
90	S07-34216	0.16	0.005
91	S07-34217	0.20	0.006
92	S07-34218	0.17	0.005
93	S07-34219	0.20	0.006
94	S07-34220	0.23	0.007
95	S07-34221	0.21	0.006
96	S07-34222	0.15	0.004
97	S07-34223	0.16	0.005
98	S07-34224	0.09	0.002
99	S07-34225	0.17	0.005
100	S07-34226	0.18	0.005
101	S07-34227	0.16	0.005
102	S07-34228	* <0.03	<0.001
103	S07-34229	0.17	0.005
104	S07-34230	0.21	0.006
105	S07-34231	0.17	0.005
106	S07-34232	0.19	0.006
107	S07-34233	0.12	0.003
108	S07-34234	0.16	0.005
109	S07-34235	0.15	0.004
110	S07-34236	0.12	0.004
111	S07-34237	0.15	0.004
112	S07-34238	0.15	0.005
113	S07-34239	0.16	0.005
114	S07-34240	* 2.04	0.059
115	S07-34241	0.20	0.006
116	S07-34242	0.15	0.004

* = 30g FA



ECO TECH LABORATORY LTD.

Jutta Jealous

B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
117	S07-34243	0.23	0.007
118	S07-34244	0.20	0.006
119	S07-34245	0.16	0.005
120	S07-34246	0.19	0.006
121	S07-34247	0.19	0.006
122	S07-34248	0.13	0.004
123	S07-34249	0.14	0.004

QC DATA:

Resplit:

1	S07-34127	<0.03	<0.001
36	S07-34162	0.09	0.003
71	S07-34197	0.11	0.003
106	S07-34232	0.15	0.004

Standard:

OXi54	1.86	0.054
OXi54	1.86	0.054
OXi54	1.86	0.054
OXi54	1.86	0.054
OXi54	1.86	0.054
OXi54	1.86	0.054
OXi54	1.86	0.054
OXi54	1.86	0.054
OXi54	1.86	0.054
OXi54	1.88	0.055

* = 30g FA

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

JJ/sa
XLS/07


ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

DO TECH LABORATORY LTD.

1041 Dallas Drive
MILLOOPS, B.C.
V6C 6T4

ICP CERTIFICATE OF ANALYSIS ANAL-07-1997

Skygold Ventures
615 - 800 W. Pender Street
Vancouver, BC
V6B 2V6

Phone: 250-573-5700

Fax : 250-573-4557

No. of samples received: 123

Sample Type: Rock

Project: Spanish Mountain

Shipment #: SMC-07-146

Submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-34127	0.4	7.73	20	385	<5	5.82	<1	19	103	131	5.65	0.76	<10	2.97	1254	<1	1.57	35	680	40	<5	<20	771	0.13	<10	194	<10	2	83
2	S07-34128	0.2	7.86	20	510	<5	5.09	<1	15	81	77	4.65	0.73	10	1.69	1060	<1	2.58	17	790	38	<5	<20	505	0.19	<10	162	<10	6	67
3	S07-34129	0.5	7.78	20	415	<5	5.40	<1	15	70	197	5.56	0.65	10	1.59	947	<1	2.40	11	1030	36	<5	<20	490	0.19	<10	154	<10	8	69
4	S07-34130	0.4	7.98	10	285	<5	5.93	<1	11	41	226	5.39	0.53	10	1.59	1037	<1	2.12	15	1260	54	5	<20	645	0.21	<10	164	<10	10	60
5	S07-34131	0.4	8.13	15	230	<5	3.88	<1	14	34	259	5.35	0.44	10	1.52	717	<1	2.51	9	1190	34	<5	<20	643	0.22	<10	186	<10	7	61
6	S07-34132	0.5	7.63	20	205	<5	4.12	<1	17	38	249	5.27	0.41	10	1.40	721	<1	2.52	17	1330	56	<5	<20	697	0.22	<10	184	<10	7	39
7	S07-34133	0.2	7.95	20	325	<5	4.73	<1	14	63	70	5.04	0.56	10	2.08	939	<1	2.25	16	730	32	<5	<20	683	0.19	<10	157	<10	6	58
8	S07-34134	4.2	4.89	235	205	5	0.49	4	9	34	648	5.23	2.19	10	1.64	323	10	0.28	20	500	96	60	<20	51	0.25	<10	51	<10	8	669
9	S07-34135	0.3	8.61	15	420	<5	4.28	<1	13	49	68	5.20	0.74	10	2.12	858	<1	2.16	15	860	34	<5	<20	734	0.19	<10	148	<10	5	80
10	S07-34136	0.6	7.71	20	1560	<5	3.95	<1	16	64	71	4.90	1.92	10	2.19	901	<1	1.25	19	690	26	5	<20	401	0.15	<10	153	<10	3	81
11	S07-34137	0.7	6.98	5	2065	<5	2.84	<1	7	87	105	3.10	1.43	20	1.61	613	1	0.53	16	580	32	<5	<20	205	0.13	<10	116	<10	7	76
12	S07-34138	1.0	6.92	35	350	<5	3.64	3	10	129	134	3.51	1.32	20	1.57	819	16	0.44	31	600	32	10	<20	225	0.11	<10	130	<10	7	116
13	S07-34139	1.4	4.77	140	100	<5	1.68	9	16	229	108	3.58	1.56	20	0.83	538	84	0.26	98	510	34	15	<20	131	0.13	<10	186	<10	4	202
14	S07-34140	0.2	4.23	80	490	<5	1.88	5	5	174	121	1.91	1.50	20	0.87	627	<1	0.24	65	300	24	10	<20	136	0.08	<10	68	<10	3	96
15	S07-34141	1.0	4.82	60	790	<5	2.76	4	7	223	96	2.47	1.56	20	1.19	798	<1	0.37	60	340	30	10	<20	186	0.12	<10	66	<10	5	92
16	S07-34142	0.4	4.97	60	910	<5	2.26	4	9	187	131	2.53	1.68	20	1.17	600	<1	0.53	59	350	34	5	<20	170	0.13	<10	73	<10	5	99
17	S07-34143	0.8	4.88	50	835	<5	1.80	4	7	145	68	2.62	1.60	20	1.19	487	<1	0.47	53	300	30	5	<20	137	0.12	<10	70	<10	3	86
18	S07-34144	1.2	3.68	60	470	<5	2.48	4	6	182	86	2.26	1.11	10	1.08	700	<1	0.35	45	260	28	5	<20	173	0.07	<10	56	<10	4	103
19	S07-34145	0.8	4.44	85	645	<5	2.24	6	7	183	89	2.21	1.39	20	1.24	571	<1	0.54	75	310	30	<5	<20	163	0.10	<10	71	<10	4	146
20	S07-34146	0.9	4.78	90	675	<5	2.42	6	8	171	83	2.60	1.38	20	1.25	572	2	0.52	68	350	32	10	<20	190	0.10	<10	83	<10	3	175
21	S07-34147	0.6	4.46	70	600	<5	2.71	6	5	192	123	2.52	1.39	20	1.37	658	41	0.40	58	420	30	10	<20	195	0.10	<10	265	<10	5	238
22	S07-34148	1.0	5.78	65	310	<5	3.06	7	11	192	153	3.57	1.46	20	1.43	593	55	0.71	59	680	38	10	<20	212	0.14	<10	339	<10	7	276
23	S07-34149	0.8	6.25	30	400	<5	3.40	3	7	138	140	4.19	1.46	20	1.58	708	25	1.16	23	800	30	5	<20	260	0.14	<10	217	<10	6	140
24	S07-34150	<0.2	1.16	<5	55	25	>10	<1	<1	3	4	0.18	0.12	<10	1.33	50	<1	0.06	79	70	12	<5	<20	4995	<0.01	<10	8	<10	<1	3
25	S07-34151	0.6	6.43	20	610	<5	2.65	3	11	152	118	4.09	1.56	20	1.31	444	32	1.35	27	950	32	5	<20	217	0.15	<10	202	<10	7	145

Et #.	Tag #	g	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
26	S07-34152	1.0	5.74	65	140	<5	2.70	8	15	165	140	4.47	1.72	20	1.21	482	54	1.28	46	590	30	5	<20	184	0.15	<10	402	<10	3	357
27	S07-34153	1.0	6.00	95	155	<5	2.50	9	17	231	104	5.15	1.77	20	1.02	437	113	0.72	61	720	32	5	<20	155	0.15	<10	464	<10	4	345
28	S07-34154	0.8	5.88	35	255	<5	2.98	4	13	125	119	3.97	1.51	20	1.16	467	36	1.47	36	950	30	5	<20	189	0.14	<10	246	<10	5	172
29	S07-34155	1.0	6.88	35	285	<5	3.01	4	13	148	111	4.78	1.64	20	1.37	527	31	1.37	31	950	42	10	<20	210	0.14	<10	231	<10	5	194
30	S07-34156	0.6	5.45	40	220	<5	2.89	4	11	219	82	4.26	1.53	20	1.31	554	22	1.03	24	770	30	10	<20	192	0.09	<10	169	<10	4	156
31	S07-34157	0.9	5.78	35	250	<5	3.05	4	13	179	104	4.25	1.49	20	1.27	602	24	1.19	32	820	30	10	<20	182	0.12	<10	246	<10	4	190
32	S07-34158	6.2	3.66	275	295	<5	0.38	2	6	43	68	3.33	2.11	<10	0.22	215	10	0.52	19	340	24	65	<20	85	0.36	<10	54	<10	8	55
33	S07-34159	0.6	6.79	20	500	<5	2.73	3	13	129	137	4.98	1.53	20	1.38	471	29	1.62	27	1070	32	5	<20	217	0.14	<10	200	<10	5	140
34	S07-34160	1.0	6.54	40	240	<5	3.10	4	12	153	101	4.41	1.52	20	1.34	488	13	1.44	25	690	32	5	<20	184	0.13	<10	216	<10	4	177
35	S07-34161	0.6	6.53	40	315	<5	3.43	5	13	94	116	4.32	1.43	20	1.44	561	24	1.41	31	590	34	10	<20	181	0.12	<10	315	<10	4	270
36	S07-34162	1.0	6.58	70	180	<5	3.61	4	20	215	166	5.79	1.60	20	1.55	582	23	1.53	36	660	38	<5	<20	187	0.13	<10	348	<10	3	314
37	S07-34163	0.8	6.37	65	200	<5	2.84	5	12	125	116	3.74	1.33	20	1.09	481	42	1.57	37	580	34	<5	<20	161	0.19	<10	417	<10	4	332
38	S07-34164	1.0	6.62	55	180	<5	3.18	7	14	206	84	4.26	1.45	10	1.35	598	50	1.16	43	640	32	15	<20	199	0.14	<10	423	<10	4	287
39	S07-34165	0.8	6.99	15	710	<5	4.58	2	8	143	62	3.28	1.33	20	1.76	833	5	1.52	12	590	32	5	<20	272	0.10	<10	92	<10	9	80
40	S07-34166	0.9	6.07	40	200	<5	3.77	4	14	85	103	4.70	1.37	20	1.54	633	20	0.98	29	700	34	5	<20	239	0.12	<10	172	<10	7	142
41	S07-34167	0.8	6.66	90	775	<5	3.92	5	21	227	99	4.24	1.43	<10	2.12	829	4	1.47	83	580	38	10	<20	273	0.11	<10	154	<10	5	127
42	S07-34168	0.8	6.36	125	500	<5	5.34	7	25	318	123	4.49	1.16	<10	2.33	1078	<1	1.08	104	540	36	15	<20	310	0.13	<10	118	<10	6	82
43	S07-34169	0.8	4.25	120	270	<5	5.01	7	22	373	117	3.28	0.66	<10	1.84	964	<1	0.99	98	1110	32	15	<20	259	0.04	<10	77	<10	7	169
44	S07-34170	0.9	6.44	125	215	<5	6.00	1	29	356	167	4.64	1.41	<10	2.51	1087	1	1.34	109	510	36	5	<20	309	0.08	<10	123	<10	6	63
45	S07-34171	1.2	4.71	105	150	<5	4.78	6	15	437	138	5.43	1.24	20	2.11	1124	64	0.53	101	860	30	20	<20	212	0.07	<10	210	<10	4	76
46	S07-34172	0.9	6.58	180	210	<5	5.87	10	32	625	115	5.78	1.29	<10	2.57	876	21	1.18	148	720	38	30	<20	280	0.07	<10	181	<10	4	158
47	S07-34173	1.2	6.20	170	215	<5	4.23	9	24	467	88	5.00	1.26	20	1.70	871	39	1.07	82	850	34	25	<20	203	0.09	<10	185	<10	5	127
48	S07-34174	1.4	5.38	100	135	<5	2.52	6	16	356	75	3.89	1.47	20	1.32	823	31	0.43	78	760	32	20	<20	126	0.09	<10	149	<10	6	105
49	S07-34175	0.9	3.85	85	165	<5	2.07	4	16	161	114	3.21	1.04	10	1.00	1192	<1	0.40	40	310	32	<5	<20	95	0.06	<10	53	<10	3	53
50	S07-34176	1.0	3.77	60	165	<5	1.95	3	13	203	125	2.66	1.08	10	1.02	1110	<1	0.41	40	310	30	10	<20	98	0.07	<10	60	<10	4	46
51	S07-34177	1.2	6.33	95	120	<5	3.24	5	21	129	178	4.03	1.62	10	1.35	1724	<1	0.79	42	370	40	5	<20	128	0.11	<10	115	<10	4	43
52	S07-34178	1.0	4.80	75	165	<5	4.55	4	16	323	116	3.51	1.17	20	1.65	2972	<1	0.61	43	710	28	10	<20	180	0.09	<10	67	<10	5	112
53	S07-34179	0.9	4.99	55	275	<5	2.07	3	15	160	102	2.60	1.24	20	1.05	890	18	0.66	32	550	28	5	<20	102	0.09	<10	61	<10	6	44
54	S07-34180	0.6	5.11	200	300	<5	4.53	10	28	772	64	4.76	0.74	<10	4.62	1986	<1	0.98	213	540	36	30	<20	209	0.06	<10	93	<10	4	134
55	S07-34181	0.7	5.45	75	155	<5	3.84	4	14	198	95	3.53	1.11	10	1.43	2001	<1	1.05	37	400	28	15	<20	155	0.11	<10	85	<10	5	42
56	S07-34182	0.4	4.19	120	505	<5	3.85	6	20	445	69	2.85	1.00	10	2.30	1464	8	0.53	111	410	28	20	<20	181	0.05	<10	79	<10	7	82
57	S07-34183	0.8	5.50	85	155	<5	3.99	5	14	294	63	3.53	1.72	20	1.91	1331	36	0.37	58	680	34	10	<20	154	0.08	<10	182	<10	6	119
58	S07-34184	2.0	5.25	85	215	<5	2.78	7	16	275	100	4.76	1.70	10	1.16	896	61	0.25	66	1130	40	15	<20	95	0.09	<10	228	<10	3	283
59	S07-34185	1.4	4.63	220	160	<5	0.24	10	7	29	38	2.65	2.89	<10	0.28	171	6	0.22	14	480	24	50	<20	37	0.33	<10	68	<10	9	49
60	S07-34186	2.2	5.33	55	210	<5	2.87	5	15	266	90	4.44	1.78	20	1.27	854	49	0.28	60	990	54	15	<20	93	0.08	<10	225	<10	4	150
61	S07-34187	2.5	5.66	75	205	<5	2.92	6	18	326	120	5.08	1.57	20	1.31	894	64	0.29	77	1080	50	20	<20	94	0.10	<10	248	<10	4	237
62	S07-34188	1.8	5.68	55	275	<5	3.09	2	14	282	83	4.18	1.49	20	1.41	987	43	0.37	46	820	38	10	<20	108	0.10	<10	216	<10	4	165
63	S07-34189	1.8	5.32	45	280	<5	2.89	4	14	348	94	4.13	1.73	20	1.29	936	45	0.31	55	820	40	20	<20	110	0.09	<10	203	<10	5	171
64	S07-34190	0.8	4.75	60	200	<5	3.56	4	15	367	46	3.00	1.42	10	1.60	1225	13	0.29	62	470	30	15	<20	142	0.08	<10	102	<10	6	89
65	S07-34191	1.6	5.37	85	215	<5	2.20	6	17	291	78	4.62	1.79	20	1.03	702	58	0.23	68	930	50	15	<20	83	0.09	<10	215	<10	6	168

Et #.	Tag #	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
66	S07-34192	1.8 5.22	70	220	<5	2.45	5	14	354	110	4.52	1.74	20	1.12	802	49	0.24	59	850	44	20	<20	92	0.09	<10	200	<10	5	194
67	S07-34193	1.4 3.23	50	85	<5	3.04	4	10	379	52	3.51	0.95	10	1.24	1027	39	0.07	44	900	32	20	<20	150	0.08	<10	146	<10	9	170
68	S07-34194	<0.2 1.18	<5	40	<5	>10	<1	<1	5	2	0.18	0.07	<10	1.64	75	<1	0.05	116	90	22	<5	<20	4847	<0.01	<10	4	<10	<1	11
69	S07-34195	2.8 5.56	90	235	<5	2.45	6	17	313	108	5.10	1.80	20	1.07	731	60	0.26	70	1050	58	15	<20	96	0.09	<10	223	<10	5	241
70	S07-34196	2.0 5.06	70	250	<5	2.72	5	15	345	104	4.52	1.67	20	1.12	806	59	0.18	62	1000	44	20	<20	113	0.10	<10	214	<10	5	235
71	S07-34197	1.4 5.30	75	215	<5	2.95	6	16	249	103	4.68	1.75	20	1.15	869	62	0.19	62	960	42	15	<20	121	0.09	<10	225	<10	5	247
72	S07-34198	1.2 6.45	120	240	<5	3.08	8	24	286	96	5.34	1.36	20	1.65	1825	47	0.57	95	930	40	20	<20	178	0.12	<10	220	<10	7	217
73	S07-34199	0.8 3.93	65	220	<5	2.70	4	19	235	94	3.78	0.62	10	1.53	2325	<1	0.52	71	370	38	10	<20	157	0.07	<10	58	<10	3	85
74	S07-34200	1.2 4.42	180	125	<5	2.58	9	18	113	69	6.92	1.10	<10	1.24	932	16	0.42	45	710	40	10	<20	126	0.06	<10	124	<10	<1	113
75	S07-34201	2.0 5.07	75	160	<5	2.77	6	15	181	73	4.29	1.58	20	1.18	783	51	0.26	68	910	48	10	<20	115	0.08	<10	218	<10	4	224
76	S07-34202	2.4 5.63	90	225	<5	3.49	7	18	247	102	5.13	1.65	20	1.41	942	63	0.27	83	930	56	20	<20	123	0.08	<10	228	<10	4	291
77	S07-34203	2.6 5.68	85	245	<5	3.30	6	18	263	90	5.10	1.77	20	1.34	920	72	0.24	80	1020	58	25	<20	123	0.08	<10	253	<10	4	215
78	S07-34204	2.0 5.29	95	150	<5	2.38	6	18	434	105	5.04	1.69	20	1.02	691	72	0.22	84	950	52	30	<20	109	0.08	<10	248	<10	4	179
79	S07-34205	2.0 4.62	70	45	<5	2.03	5	15	265	129	4.34	1.69	20	0.96	574	64	0.21	72	860	60	15	<20	103	0.08	<10	248	<10	5	162
80	S07-34206	2.6 5.47	80	285	<5	3.80	6	15	278	85	5.04	1.72	20	1.62	1124	63	0.27	75	1010	62	25	<20	154	0.08	<10	253	<10	5	264
81	S07-34207	2.6 5.37	70	125	<5	3.04	6	17	319	102	4.93	1.61	20	1.26	909	66	0.25	77	920	58	25	<20	127	0.09	<10	239	<10	6	271
82	S07-34208	2.4 5.36	60	140	<5	3.16	6	16	246	109	4.82	1.57	20	1.25	953	66	0.24	75	1030	62	20	<20	133	0.11	<10	243	<10	6	294
83	S07-34209	1.0 5.05	85	295	<5	3.03	7	17	264	57	4.77	1.47	20	1.14	892	64	0.26	72	1030	38	20	<20	132	0.08	<10	227	<10	4	270
84	S07-34210	0.8 5.25	120	200	<5	3.31	7	19	314	70	5.00	1.52	20	1.27	920	61	0.29	79	930	44	15	<20	139	0.09	<10	218	<10	4	191
85	S07-34211	1.0 6.04	110	255	<5	3.42	7	21	319	84	5.11	1.68	20	1.35	1030	67	0.38	80	1030	46	20	<20	152	0.11	<10	242	<10	4	207
86	S07-34212	1.4 5.79	100	250	<5	3.04	7	20	184	63	5.28	1.77	20	1.25	897	78	0.35	82	1130	46	20	<20	126	0.10	<10	259	<10	3	243
87	S07-34213	1.2 7.37	185	250	<5	7.41	10	30	572	242	5.17	1.65	10	2.54	2171	26	0.85	161	890	68	30	<20	304	0.09	<10	187	<10	5	260
88	S07-34214	2.2 5.61	90	265	<5	3.80	6	21	258	122	4.87	1.56	20	1.62	1287	57	0.37	87	960	56	20	<20	175	0.09	<10	235	<10	5	206
89	S07-34215	2.2 6.02	80	150	<5	2.85	7	19	385	162	5.12	1.67	20	1.17	899	62	0.30	79	1020	60	20	<20	127	0.12	<10	246	<10	4	321
90	S07-34216	2.2 5.18	70	145	<5	3.06	6	15	324	114	4.62	1.53	20	1.33	995	54	0.30	72	810	52	15	<20	143	0.09	<10	219	<10	4	250
91	S07-34217	1.8 4.98	65	80	<5	2.81	3	17	132	112	4.51	1.53	20	1.23	829	52	0.32	62	780	54	10	<20	125	0.10	<10	232	<10	3	246
92	S07-34218	2.6 5.28	80	55	<5	2.60	7	17	237	99	4.99	1.56	20	1.10	653	59	0.34	79	880	52	15	<20	118	0.09	<10	240	<10	3	332
93	S07-34219	2.4 5.07	65	85	<5	3.07	5	17	269	163	4.62	1.50	10	1.31	801	53	0.37	72	890	54	20	<20	142	0.09	<10	214	<10	4	216
94	S07-34220	2.4 5.24	70	80	<5	3.29	5	19	301	134	4.98	1.48	20	1.38	836	59	0.36	76	940	54	25	<20	153	0.09	<10	222	<10	4	224
95	S07-34221	2.8 5.34	65	125	<5	2.43	6	19	521	98	4.92	1.60	20	1.11	738	69	0.34	75	1020	56	30	<20	134	0.11	<10	257	<10	5	291
96	S07-34222	2.2 5.73	70	90	<5	3.40	7	18	131	124	4.91	1.67	20	1.48	923	58	0.42	75	1130	50	15	<20	179	0.11	<10	252	<10	5	286
97	S07-34223	2.2 5.33	105	110	<5	4.25	7	19	185	107	4.68	1.52	20	1.77	1375	48	0.49	93	970	52	20	<20	213	0.10	<10	252	<10	5	253
98	S07-34224	1.6 5.37	125	95	<5	3.93	3	21	276	112	4.94	1.59	10	1.66	930	50	0.46	111	840	42	10	<20	210	0.09	<10	270	<10	6	206
99	S07-34225	2.2 5.49	135	135	<5	4.76	4	25	196	134	6.08	1.55	20	1.97	1274	50	0.51	114	950	86	15	<20	238	0.09	<10	275	<10	6	260
100	S07-34226	2.4 5.10	80	70	<5	2.74	4	20	300	102	4.70	1.50	20	1.19	798	54	0.30	79	870	56	10	<20	153	0.11	<10	265	<10	5	274
101	S07-34227	2.6 4.27	60	70	<5	2.33	5	15	620	74	4.16	1.32	10	0.96	626	67	0.33	74	910	96	35	<20	116	0.08	<10	225	<10	3	151
102	S07-34228	<0.2 0.06	<5	25	<5	>10	<1	<1	2	<1	0.04	<0.01	<10	1.59	14	<1	0.01	120	30	16	<5	<20	4815	<0.01	<10	5	<10	<1	4
103	S07-34229	2.9 5.02	85	125	<5	4.21	6	18	378	91	5.24	1.59	20	1.81	1076	58	0.45	93	880	58	30	<20	217	0.09	<10	250	<10	6	223
104	S07-34230	2.6 5.22	75	110	<5	3.99	6	18	254	70	4.84	1.54	20	1.55	990	56	0.38	88	1240	54	20	<20	190	0.09	<10	244	<10	6	208
105	S07-34231	2.6 5.63	85	125	<5	4.30	7	19	305	90	5.35	1.65	20	1.74	1204	64	0.43	93	1020	58	20	<20	196	0.10	<10	248	<10	5	294

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	Y	Zn			
106	S07-34232	1.8	5.83	100	55	<5	5.50	4	25	348	140	5.53	1.45	20	2.20	1656	30	0.47	100	1280	54	15	<20	283	0.15	<10	260	<10	9	340
107	S07-34233	1.8	5.65	85	60	5	4.46	3	21	173	100	4.78	1.53	20	2.00	1254	26	0.62	83	1220	48	10	<20	258	0.17	<10	289	<10	9	256
108	S07-34234	1.6	5.10	80	55	<5	4.53	3	21	257	126	4.22	1.37	20	2.15	1357	21	0.74	77	1090	40	10	<20	270	0.12	<10	247	<10	9	219
109	S07-34235	1.7	6.25	125	55	<5	5.96	4	26	249	118	5.75	1.57	20	2.31	1618	28	0.64	124	1280	62	10	<20	296	0.16	<10	276	<10	11	320
110	S07-34236	2.2	5.72	85	60	<5	3.72	3	23	355	90	4.99	1.40	20	1.57	1205	33	0.59	87	1090	46	10	<20	183	0.12	<10	277	<10	8	276
111	S07-34237	2.6	5.25	75	30	10	2.86	4	22	353	116	5.23	1.53	20	1.26	992	39	0.46	86	1140	50	15	<20	152	0.14	<10	314	<10	7	332
112	S07-34238	2.2	5.52	75	35	<5	3.47	4	21	178	146	4.82	1.47	20	1.43	1528	29	0.66	71	1070	48	10	<20	176	0.14	<10	263	<10	8	336
113	S07-34239	2.6	5.19	65	35	<5	2.78	3	20	228	85	4.72	1.35	20	1.15	1132	32	0.50	70	1080	60	15	<20	139	0.14	<10	254	<10	7	303
114	S07-34240	4.6	4.76	265	75	<5	0.46	5	13	39	597	5.32	1.95	10	1.72	431	10	0.27	26	570	102	50	<20	64	0.32	<10	62	<10	11	714
115	S07-34241	3.0	5.15	75	35	10	2.90	4	25	261	100	5.03	1.41	20	1.18	1269	36	0.55	81	1110	70	15	<20	162	0.15	<10	277	<10	8	354
116	S07-34242	2.8	4.47	60	35	15	2.76	3	18	279	108	4.19	1.30	20	1.16	1083	27	0.56	66	930	54	15	<20	141	0.12	<10	245	<10	7	273
117	S07-34243	2.6	4.94	60	40	10	2.79	3	19	203	87	4.29	1.38	20	1.17	1065	31	0.47	64	1030	54	15	<20	152	0.13	<10	269	<10	7	280
118	S07-34244	3.2	4.87	70	30	5	2.61	4	20	199	102	4.67	1.45	20	1.15	1049	36	0.52	74	1020	60	15	<20	130	0.12	<10	280	<10	6	315
119	S07-34245	2.6	5.65	80	50	<5	3.93	4	25	336	115	5.36	1.39	20	1.53	1716	33	0.60	81	1260	62	15	<20	182	0.13	<10	260	<10	7	302
120	S07-34246	2.0	5.56	65	45	5	4.24	3	22	211	196	4.30	1.21	20	1.60	1786	17	0.92	63	890	48	10	<20	201	0.13	<10	177	<10	7	188
121	S07-34247	2.6	5.31	65	35	15	2.88	3	20	264	79	4.73	1.50	20	1.23	1178	34	0.53	66	1050	54	15	<20	154	0.12	<10	259	<10	6	292
122	S07-34248	2.2	5.20	70	45	<5	3.19	4	22	375	75	4.87	1.37	20	1.09	1229	35	0.36	74	1250	52	15	<20	161	0.16	<10	259	<10	8	351
123	S07-34249	3.0	5.49	70	35	<5	2.99	3	21	336	73	4.90	1.53	20	1.20	1077	38	0.51	72	1140	56	15	<20	143	0.11	<10	287	<10	6	253

IC DATA:**Repeat:**

1	S07-34127	0.4	7.55	30	355	<5	5.66	<1	20	95	138	5.69	0.74	<10	2.91	1216	<1	1.66	36	660	36	<5	<20	721	0.13	<10	190	<10	2	83
10	S07-34136	0.6	8.40	10	1520	<5	3.80	<1	15	62	70	4.97	1.96	10	2.11	943	<1	1.24	20	750	28	5	<20	386	0.16	<10	153	<10	2	86
19	S07-34145	0.8	4.52	95	655	<5	2.24	6	7	188	86	2.20	1.41	20	1.27	569	<1	0.54	79	310	32	10	<20	166	0.10	<10	71	<10	4	152
36	S07-34162	1.1	6.79	70	185	<5	3.80	5	21	224	169	5.91	1.40	20	1.58	609	22	1.50	37	700	34	<5	<20	198	0.15	<10	358	<10	3	341
45	S07-34171	1.2	4.75	115	140	<5	5.14	6	15	450	144	5.52	1.27	20	2.19	1153	68	0.53	106	910	28	15	<20	221	0.07	<10	217	<10	4	81
54	S07-34180	0.6	5.12	205	300	<5	4.50	2	28	733	61	4.75	0.77	<10	4.72	2089	<1	1.00	215	480	36	30	<20	213	0.06	<10	96	<10	4	140
71	S07-34197	3.0	5.50	85	215	<5	2.88	7	16	247	106	4.77	1.71	20	1.17	903	64	0.20	66	990	44	20	<20	122	0.08	<10	222	<10	4	263
80	S07-34206	2.6	5.37	80	310	<5	3.74	3	15	272	83	5.06	1.64	20	1.58	1128	62	0.26	68	920	62	15	<20	148	0.09	<10	242	<10	5	246
89	S07-34215	2.0	5.91	70	150	<5	2.86	6	17	363	165	4.67	1.59	20	1.11	824	59	0.27	73	930	54	25	<20	124	0.11	<10	246	<10	4	296
106	S07-34232	1.8	5.88	85	55	<5	5.46	4	22	345	140	5.02	1.52	20	2.18	1681	27	0.51	96	1220	46	15	<20	283	0.11	<10	238	<10	8	349
115	S07-34241	2.8	5.00	70	35	10	3.08	4	22	270	103	4.78	1.39	20	1.10	1169	33	0.53	75	1020	64	15	<20	147	0.13	<10	257	<10	8	355

Resplit:

1	S07-34127	0.4	7.45	30	405	<5	5.82	<1	20	100	119	5.62	0.76	<10	2.99	1207	<1	1.64	36	630	28	5	<20	775	0.14	<10	193	<10	2	88
36	S07-34162	1.0	7.14	75	190	<5	3.69	7	19	221	162	5.74	1.71	20	1.45	578	23	1.45	33	640	38	<5	<20	196	0.14	<10	377	<10	4	355
71	S07-34197	1.2	5.01	80	210	<5	3.06	4	15	244	104	4.56	1.58	20	1.14	864	57	0.18	59	930	42	10	<20	117	0.09	<10	210	<10	4	250
106	S07-34232	2.0	5.81	95	55	10	5.52	4	22	346	147	5.06	1.53	20	2.15	1607	30	0.45	88	1280	46	10	<20	284	0.15	<10	240	<10	7	344

Standard:

3std-3		0.4	5.97	20	1225	<5	2.19	2	13	58	46	4.17	1.46	30	1.18	2071	7	1.28	29	1560	46	10	<20	230	0.29	<10	114	<10	29	165
3std-3		0.5	5.71	25	1295	<5	2.41	2	15	60	41	4.12	1.40	30	1.18	2265	10	1.20	34	1640	52	10	<20	235	0.31	<10	114	<10	31	189
3std-3		0.5	5.87	25	1390	<5	2.50	1	17	62	42	4.21	1.39	40	1.31	2584	10	1.17	32	1690	56	10	<20	268	0.35	<10	121	<10	33	206
3std-3		0.4	5.93	25	1405	<5	2.57	1	17	62	42	4.19	1.39	30	1.31	2543	6	1.15	32	1670	54	5	<20	267	0.35	<10	119	<10	32	206


ICP: 4 ACID DIGEST/ICP-FINISH

AG: 4 ACID DIGEST/AA-FINISH


JJ/nl

#/TD1997AS/TD1997BS

XLS/07



ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2281

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

4-Mar-08

Attention: Bob Singh

No. of samples received: 25
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-148
Samples submitted by: Tasha Gainer

Metallic Assays


ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-34250	0.12	0.003
2	S07-34251	0.14	0.004
3	S07-34252	0.12	0.003
4	S07-34253	0.11	0.003
5	S07-34254	0.29	0.008
6	S07-34255	0.11	0.003
7	S07-34256	0.11	0.003
8	S07-34257	0.15	0.004
9	S07-34258	0.09	0.003
10	S07-34259	0.15	0.004
11	S07-34260	* <0.03	<0.001
12	S07-34261	0.26	0.008
13	S07-34262	0.16	0.005
14	S07-34263	0.21	0.006
15	S07-34264	0.18	0.005
16	S07-34265	0.20	0.006
17	S07-34266	0.17	0.005
18	S07-34267	0.18	0.005
19	S07-34268	0.15	0.004
20	S07-34269	0.22	0.006
21	S07-34270	0.41	0.012
22	S07-34271	0.35	0.010
23	S07-34272	0.16	0.005
24	S07-34273	0.03	0.001
25	S07-34274	0.05	0.002

GC DATA:

Resplit:

1	S07-34250	0.12	0.003
---	-----------	------	-------

* = 30g FA


ECOTECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Skygold Ventures AK7-2281

4-Mar-08

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
Standard:			
OXI54		1.87	0.055
OXI54		1.88	0.055

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw
XLS/07



ECO TECH LABORATORY LTD.

Julia Jealouse
B.C. Certified Assayer

O TECH LABORATORY LTD.

141 Dallas Drive

MLOOPS, B.C.

V6T4

Phone: 250-573-5700

Fax: 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK-2281

Skygold Ventures

615 - 800 W. Pender Street

Vancouver, BC

V6B 2V6

No. of samples received: 25

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-148

Samples submitted by: Tasha Gainer

Concentrations in ppm unless otherwise reported

Lot #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-34250	2.2	4.67	15	95	<5	2.79	3	16	189	67	4.21	1.64	20	1.23	1042	24	0.37	67	1140	56	10	<20	193	0.12	<10	237	<10	8	241
2	S07-34251	2.6	5.19	25	85	<5	3.38	2	18	208	77	4.48	1.84	20	1.44	1199	29	0.50	73	1210	62	10	<20	210	0.11	<10	264	<10	7	244
3	S07-34252	2.0	4.88	25	110	<5	4.61	2	22	313	116	4.56	1.68	20	1.83	1563	23	0.52	89	1240	54	10	<20	285	0.13	<10	236	<10	8	224
4	S07-34253	2.2	4.90	20	65	<5	2.89	2	18	351	73	4.32	1.85	20	1.17	878	25	0.40	69	1120	54	10	<20	155	0.10	<10	256	<10	6	218
5	S07-34254	2.0	4.82	15	95	<5	3.76	3	17	230	69	4.16	1.68	20	1.45	1157	27	0.48	63	1150	44	5	<20	205	0.11	<10	251	<10	6	247
6	S07-34255	1.6	5.33	20	85	<5	4.33	3	19	206	103	4.32	1.84	20	1.80	1511	23	0.65	83	1200	44	5	<20	279	0.13	<10	264	<10	8	251
7	S07-34256	1.0	4.43	20	95	<5	3.53	1	19	285	80	3.89	1.48	20	1.48	1256	15	0.69	67	1120	36	5	<20	228	0.10	<10	208	<10	7	151
8	S07-34257	0.8	5.75	25	245	<5	6.18	<1	21	234	150	3.81	1.61	10	2.72	2012	2	1.55	83	1000	36	<5	<20	474	0.14	<10	153	<10	10	83
9	S07-34258	1.4	4.50	15	105	<5	2.95	3	18	257	55	4.21	1.61	20	1.28	1152	30	0.62	68	1190	42	5	<20	184	0.11	<10	256	<10	7	249
10	S07-34259	2.6	5.18	20	60	<5	3.04	3	17	176	83	4.24	1.87	20	1.32	1001	27	0.46	70	1200	58	10	<20	179	0.09	<10	281	<10	7	247
11	S07-34260	<0.2	0.04	<5	15	<5	>10	<1	<1	<1	1	0.03	<0.01	<10	1.67	23	<1	<0.01	19	40	4	<5	<20	6334	<0.01	<10	2	<10	<1	2
12	S07-34261	2.6	4.55	20	70	<5	2.88	2	17	159	80	4.07	1.60	20	1.23	980	20	0.51	68	1300	52	10	<20	179	0.10	<10	263	<10	7	215
13	S07-34262	3.2	5.43	20	100	<5	2.99	2	19	128	80	4.23	1.99	20	1.34	1012	28	0.56	75	1250	64	10	<20	186	0.11	<10	296	<10	8	211
14	S07-34263	3.2	5.37	25	60	<5	2.63	2	18	133	86	4.24	2.00	20	1.17	896	31	0.50	78	1360	60	10	<20	162	0.11	<10	309	<10	9	231
15	S07-34264	2.6	4.98	20	75	<5	2.83	3	17	259	67	4.48	1.89	20	1.30	1006	27	0.29	72	1230	60	10	<20	175	0.10	<10	251	<10	7	287
16	S07-34265	2.0	4.50	15	60	<5	3.47	3	19	174	95	4.37	1.72	20	1.55	1133	22	0.35	95	950	44	10	<20	208	0.10	<10	265	<10	7	279
17	S07-34266	2.0	4.71	20	70	<5	3.84	3	23	210	97	4.37	1.65	20	1.67	1212	25	0.63	118	1000	44	10	<20	221	0.10	<10	265	<10	8	290
18	S07-34267	2.0	4.25	15	70	<5	3.55	2	17	241	72	3.91	1.44	20	1.52	1142	16	0.69	82	930	44	10	<20	203	0.09	<10	215	<10	7	199
19	S07-34268	2.4	4.63	20	70	<5	2.46	2	16	126	64	3.91	1.80	20	1.14	808	23	0.41	73	1150	52	10	<20	145	0.12	<10	306	<10	7	244
20	S07-34269	2.2	4.38	15	45	<5	2.48	3	15	226	59	4.05	1.65	10	1.10	812	22	0.37	74	1090	52	10	<20	138	0.11	<10	292	<10	6	251
21	S07-34270	5.6	4.56	25	90	<5	2.80	3	17	200	64	4.69	1.70	10	1.37	1049	29	0.48	82	1190	84	15	<20	170	0.10	<10	274	<10	6	274
22	S07-34271	4.6	4.43	20	95	<5	2.51	3	18	193	62	4.28	1.69	10	1.18	992	30	0.46	80	1260	76	15	<20	146	0.11	<10	310	<10	6	286
23	S07-34272	2.0	4.04	20	85	<5	3.80	2	15	235	41	3.82	1.51	10	1.72	1439	17	0.42	65	1010	42	10	<20	221	0.09	<10	227	<10	6	160
24	S07-34273	0.8	5.41	30	330	<5	5.83	<1	22	394	81	4.15	1.57	20	3.08	1836	9	1.15	94	1140	48	10	<20	394	0.13	<10	180	<10	9	117
25	S07-34274	1.0	5.07	20	90	<5	3.73	2	18	278	58	4.10	1.77	20	1.69	1314	24	0.69	70	1030	38	5	<20	208	0.12	<10	227	<10	7	195

DATA:


Repeat:

1	S07-34250	2.4	4.75	20	110	<5	2.93	3	16	190	68	4.18	1.70	20	1.27	1084	25	0.40	67	1170	54	10	<20	198	0.11	<10	249	<10	7	255
10	S07-34259	2.4	5.06	20	70	<5	2.90	3	17	179	83	4.20	1.87	20	1.33	996	26	0.46	68	1180	58	10	<20	181	0.09	<10	286	<10	6	246


It #.	Tag #	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
<i>split:</i>																														
1	S07-34250	2.1	4.77	20	95	<5	2.90	3	17	195	69	4.39	1.66	20	1.31	1145	25	0.38	71	1210	54	10	<20	205	0.11	<10	247	<10	7	254
<i>standard:</i>																														
d3		0.4	5.86	20	1430	30	2.35	<1	16	64	46	4.27	1.39	40	1.30	2602	6	1.08	33	1690	56	5	<20	264	0.35	<10	103	<10	32	204
d3		0.6	5.88	25	1490	35	2.33	1	17	65	43	4.30	1.43	40	1.33	2555	6	1.10	33	1680	54	5	<20	254	0.36	<10	128	<10	36	210

1: 4 ACID DIGEST/ICP-FINISH
 2: 4 ACID DIGEST/AA-FINISH

1W
 2281s
 3/07



ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 1965

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

10-Dec-07


Attention: Bob Singh

No. of samples received: 49
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-145
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-05443	<0.03	<0.001
2	S07-05444	<0.03	<0.001
3	S07-05445	<0.03	<0.001
4	S07-05446	<0.03	<0.001
5	S07-05447	<0.03	<0.001
6	S07-05448	<0.03	<0.001
7	S07-05449	<0.03	<0.001
8	S07-05450	<0.03	<0.001
9	S07-05451	<0.03	<0.001
10	S07-05452	<0.03	<0.001
11	S07-05453	* <0.03	<0.001
12	S07-05454	<0.03	<0.001
13	S07-05455	<0.03	<0.001
14	S07-05456	<0.03	<0.001
15	S07-05457	<0.03	<0.001
16	S07-05458	<0.03	<0.001
17	S07-05459	* 2.10	0.061
18	S07-05460	<0.03	<0.001
19	S07-05461	<0.03	<0.001
20	S07-05462	0.03	0.001
21	S07-05463	0.03	0.001
22	S07-05464	0.03	0.001
23	S07-05465	0.08	0.002
24	S07-05466	<0.03	<0.001
25	S07-05467	0.03	0.001

* = 30g FA


ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	S07-05468	<0.03	<0.001
27	S07-05469	1.56	0.045
28	S07-05470	*	<0.001
29	S07-05471	<0.03	<0.001
30	S07-05472	<0.03	<0.001
31	S07-05473	<0.03	<0.001
32	S07-05474	<0.03	<0.001
33	S07-05475	<0.03	<0.001
34	S07-05476	<0.03	<0.001
35	S07-05477	<0.03	<0.001
36	S07-05478	<0.03	<0.001
37	S07-05479	<0.03	<0.001
38	S07-05480	<0.03	<0.001
39	S07-05481	<0.03	<0.001
40	S07-05482	<0.03	<0.001
41	S07-05483	<0.03	<0.001
42	S07-05484	<0.03	<0.001
43	S07-05485	<0.03	<0.001
44	S07-05486	<0.03	<0.001
45	S07-05487	<0.03	<0.001
46	S07-05488	<0.03	<0.001
47	S07-05489	<0.03	<0.001
48	S07-05490	<0.03	<0.001
49	S07-05491	<0.03	<0.001

QC DATA:**Resplit:**

1	S07-05443	<0.03	<0.001
36	S07-05478	<0.03	<0.001

Standard:

OXi54	1.88	0.055
OXi54	1.84	0.054
OXi54	1.86	0.054
OXi54	1.87	0.055

* = 30g FA

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

JJ/sa
XLS/07


 ECO TECH LABORATORY LTD.

 Jutta Jealous
 B.C. Certified Assayer

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 2007-1965

Skygold Ventures
615 - 800 W. Pender Street
Vancouver, BC
V6B 2V6

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 49
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-145
Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-05443	<0.2	5.93	95	2225	<5	1.04	<1	40	249	80	5.29	1.60	20	1.43	4688	<1	0.73	104	890	76	<5	<20	102	0.27	<10	103	<10	10	224
2	S07-05444	0.2	4.46	105	1975	<5	0.67	<1	29	267	168	3.99	1.43	20	1.02	3756	<1	0.44	79	610	54	<5	<20	77	0.21	<10	140	<10	8	214
3	S07-05445	<0.2	5.71	10	2895	<5	0.79	<1	6	245	31	1.93	1.67	10	1.32	3077	1	0.85	18	430	38	<5	<20	128	0.16	<10	39	<10	7	153
4	S07-05446	<0.2	6.77	5	3250	<5	0.98	<1	5	272	25	2.07	2.04	20	1.30	3028	1	1.12	19	1310	36	<5	<20	145	0.20	<10	33	<10	12	119
5	S07-05447	0.2	5.27	<5	2025	<5	0.99	<1	4	191	20	2.00	1.66	10	1.08	2687	<1	0.91	14	270	28	<5	<20	113	0.12	<10	24	<10	6	87
6	S07-05448	<0.2	6.09	10	2265	<5	1.01	<1	4	283	27	2.03	1.98	20	1.06	1809	<1	0.89	18	380	30	<5	<20	114	0.13	<10	24	<10	9	77
7	S07-05449	0.2	5.37	75	1555	5	1.59	<1	23	246	103	4.18	1.73	20	2.04	2693	<1	0.49	80	430	36	<5	<20	132	0.11	<10	49	<10	9	103
8	S07-05450	<0.2	4.80	85	1195	<5	2.37	<1	35	581	112	4.87	1.60	10	3.93	3120	<1	0.59	207	560	30	5	<20	232	0.10	<10	92	<10	7	156
9	S07-05451	<0.2	4.71	15	1975	<5	0.76	<1	7	157	27	1.87	1.67	20	0.99	1508	<1	0.45	20	230	34	<5	<20	84	0.12	<10	45	<10	8	54
10	S07-05452	<0.2	4.54	5	2255	5	0.52	<1	5	133	19	1.88	1.88	20	1.23	1441	<1	0.67	13	300	24	<5	<20	68	0.12	<10	33	<10	8	43
11	S07-05453	<0.2	7.76	<5	550	<5	2.93	<1	11	84	90	4.79	1.02	10	1.32	845	4	2.26	29	810	28	<5	<20	322	0.40	<10	108	<10	20	61
12	S07-05454	0.2	6.01	10	2200	<5	0.87	<1	6	152	72	1.99	1.95	20	1.22	1075	<1	0.69	22	340	30	<5	<20	83	0.17	<10	27	<10	7	40
13	S07-05455	0.4	7.12	90	1955	<5	1.48	<1	21	299	231	4.02	2.07	10	2.71	1484	<1	0.31	102	520	32	5	<20	107	0.17	<10	51	<10	11	58
14	S07-05456	<0.2	5.04	125	1210	10	3.17	<1	28	524	24	3.86	1.89	10	5.05	1593	<1	0.36	191	450	24	5	<20	295	0.07	<10	87	<10	7	53
15	S07-05457	<0.2	6.06	70	1620	<5	2.09	<1	16	219	142	3.47	1.90	20	3.16	1594	<1	0.23	104	600	32	<5	<20	146	0.10	<10	48	<10	8	105
16	S07-05458	<0.2	5.70	30	2055	<5	1.72	<1	12	109	35	2.99	1.93	20	2.35	1596	3	1.09	42	600	42	<5	<20	164	0.15	<10	58	<10	7	91
17	S07-05459	4.7	4.45	220	250	<5	0.51	2	13	37	610	5.20	2.14	10	1.68	414	9	0.21	25	520	96	40	<20	66	0.31	<10	56	<10	12	745
18	S07-05460	<0.2	4.42	40	1490	5	2.09	<1	19	114	121	2.94	1.41	20	1.20	1763	3	0.78	49	520	36	<5	<20	145	0.11	<10	79	<10	6	64
19	S07-05461	0.4	4.37	45	1910	<5	1.23	<1	19	93	55	3.22	1.57	20	1.28	1739	2	0.34	40	370	34	<5	<20	107	0.13	<10	84	<10	6	83
20	S07-05462	0.7	4.83	70	1900	5	0.75	<1	26	82	103	3.57	1.80	20	1.26	1847	2	0.50	70	460	38	<5	<20	72	0.16	<10	68	<10	6	101
21	S07-05463	0.8	4.23	75	1840	<5	1.03	<1	29	54	123	3.79	1.71	20	1.12	2231	<1	0.61	58	420	46	<5	<20	90	0.13	<10	58	<10	6	108
22	S07-05464	0.5	4.78	60	1985	<5	1.21	<1	24	45	55	3.27	1.63	20	1.07	2035	<1	0.58	50	390	44	<5	<20	102	0.15	<10	75	<10	5	110
23	S07-05465	0.6	5.32	65	2305	<5	1.42	<1	26	71	62	3.64	1.48	20	1.31	2277	<1	0.53	54	440	48	<5	<20	119	0.15	<10	90	<10	7	94
24	S07-05466	0.8	4.79	75	1830	<5	0.82	<1	30	79	94	3.86	1.48	20	1.18	2600	<1	0.68	66	470	42	<5	<20	78	0.16	<10	68	<10	7	103
25	S07-05467	0.7	5.26	40	2070	<5	0.93	<1	15	53	76	3.65	1.67	20	1.52	3033	<1	0.71	36	550	70	<5	<20	85	0.17	<10	90	<10	6	194

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
26	S07-05468	<0.2	5.91	55	1945	<5	1.07	<1	17	107	71	3.30	1.31	20	1.99	2541	<1	0.82	48	550	28	<5	<20	100	0.17	<10	75	<10	5	99
27	S07-05469	0.8	5.20	30	1795	<5	0.92	2	13	120	162	2.56	1.43	20	1.29	1996	4	0.83	25	480	152	<5	<20	93	0.16	<10	52	<10	6	290
28	S07-05470	<0.2	1.14	<5	40	<5	>10	<1	<1	3	9	0.18	0.08	<10	1.54	65	<1	0.04	24	50	10	<5	<20	4822	<0.01	<10	<1	<10	<1	1
29	S07-05471	0.4	5.73	140	1635	<5	2.22	<1	31	172	72	4.41	1.25	20	2.65	2342	<1	0.30	108	570	34	<5	<20	178	0.17	<10	103	<10	7	89
30	S07-05472	0.6	4.93	95	1090	<5	1.04	<1	28	370	96	4.19	1.40	20	1.66	2203	<1	0.36	74	410	38	<5	<20	84	0.18	<10	107	<10	6	111
31	S07-05473	0.5	5.59	100	1030	<5	1.19	<1	29	300	118	4.39	1.24	20	1.74	2124	<1	0.95	78	510	36	<5	<20	102	0.18	<10	107	<10	6	107
32	S07-05474	<0.2	6.50	175	1195	<5	3.48	<1	42	516	47	5.59	1.38	10	4.25	3024	<1	0.61	185	690	36	10	<20	232	0.16	<10	171	<10	8	118
33	S07-05475	0.4	5.10	110	1075	<5	1.17	<1	29	202	73	3.80	1.33	20	1.88	1878	<1	0.35	79	520	34	<5	<20	91	0.20	<10	141	<10	8	64
34	S07-05476	0.6	5.18	100	930	<5	0.88	<1	30	219	72	3.89	1.31	20	1.80	1871	<1	0.35	78	460	78	<5	<20	70	0.19	<10	108	<10	8	66
35	S07-05477	0.5	5.47	110	900	<5	1.52	<1	34	276	65	4.42	1.33	20	2.49	2134	<1	0.45	99	610	44	<5	<20	100	0.17	<10	108	<10	9	102
36	S07-05478	<0.2	3.02	80	550	<5	1.78	<1	15	334	7	2.09	1.04	<10	2.09	1732	<1	0.16	89	210	18	5	<20	102	0.05	<10	45	<10	5	52
37	S07-05479	0.2	2.99	<5	965	<5	0.54	<1	3	57	23	1.09	1.12	<10	0.72	934	<1	0.17	9	160	24	<5	<20	38	0.08	<10	27	<10	4	31
38	S07-05480	0.2	3.10	<5	1000	<5	0.50	<1	3	75	18	1.10	1.12	<10	0.69	918	<1	0.17	7	150	22	<5	<20	35	0.09	<10	24	<10	4	26
39	S07-05481	<0.2	3.12	<5	925	<5	0.35	<1	3	79	14	1.10	1.15	<10	0.68	844	<1	0.25	6	150	16	<5	<20	29	0.10	<10	13	<10	4	36
40	S07-05482	0.2	2.75	<5	805	<5	0.41	<1	2	76	14	0.99	1.04	<10	0.60	824	<1	0.23	5	140	18	<5	<20	34	0.09	<10	17	<10	4	29
41	S07-05483	<0.2	2.79	<5	715	<5	0.33	<1	2	10	17	1.01	1.10	<10	0.64	622	<1	0.37	5	150	20	<5	<20	31	0.08	<10	11	<10	3	27
42	S07-05484	0.2	2.96	30	475	5	0.92	<1	14	153	40	1.75	1.00	<10	1.52	996	<1	0.46	82	200	20	<5	<20	56	0.07	<10	27	<10	5	46
43	S07-05485	<0.2	3.00	10	180	<5	1.73	<1	15	230	15	2.21	0.72	<10	2.68	852	<1	0.42	104	300	16	<5	<20	104	0.04	<10	56	<10	4	44
44	S07-05486	<0.2	2.66	10	140	<5	1.42	<1	8	75	2	1.49	0.59	10	1.78	525	<1	0.38	52	220	16	<5	<20	94	0.05	<10	25	<10	5	19
45	S07-05487	<0.2	3.37	30	105	<5	2.22	<1	19	307	20	2.94	0.60	<10	3.66	862	<1	0.57	132	400	20	5	<20	119	0.04	<10	76	<10	4	41
46	S07-05488	<0.2	2.66	40	75	<5	3.04	<1	28	468	3	2.76	0.50	<10	4.11	996	<1	0.37	244	290	14	5	<20	135	0.02	<10	55	<10	5	57
47	S07-05489	<0.2	3.28	45	240	<5	1.33	<1	12	271	2	2.73	0.93	<10	3.39	713	<1	0.43	125	280	14	<5	<20	86	0.04	<10	40	<10	5	42
48	S07-05490	<0.2	3.26	85	360	<5	2.77	<1	21	290	20	2.26	1.04	<10	3.18	1082	<1	0.42	147	310	18	5	<20	150	0.04	<10	51	<10	5	37
49	S07-05491	0.3	3.18	110	460	<5	1.34	<1	16	286	46	1.78	1.02	<10	2.19	714	<1	0.35	138	170	20	10	<20	84	0.06	<10	25	<10	6	29

QC DATA:

Repeat:

1	S07-05443	<0.2	5.68	95	2250	5	0.93	<1	43	241	89	5.12	1.71	20	1.66	4701	<1	0.74	108	800	78	<5	<20	95	0.21	<10	94	<10	10	230
10	S07-05452	<0.2	4.74	<5	2265	<5	0.55	<1	3	129	19	1.72	1.76	<10	1.16	1389	<1	0.57	10	290	22	<5	<20	80	0.09	<10	31	<10	9	51
19	S07-05461	0.4	4.59	25	1735	<5	1.16	<1	11	96	59	2.98	1.45	10	1.19	1704	1	0.32	34	400	34	<5	<20	96	0.11	<10	77	<10	4	79
36	S07-05478	<0.2	2.99	75	560	<5	1.79	<1	15	364	7	2.10	1.16	<10	2.09	1736	<1	0.17	89	230	18	<5	<20	103	0.05	<10	46	<10	4	55

Resplit:


1	S07-05443	<0.2	5.75	90	2220	<5	0.99	<1	39	210	81	5.23	1.68	20	1.51	4699	<1	0.77	98	870	76	<5	<20	98	0.26	<10	95	<10	9	224
36	S07-05478	<0.2	2.94	80	625	<5	1.81	<1	16	338	6	2.13	1.03	<10	2.18	1799	<1	0.16	97	220	18	5	<20	105	0.05	<10	43	<10	4	53

Standard:

STSD3		0.5	5.43	26	1395	<5	2.38	<1	17	37	34	4.27	1.27	20	1.21	2420	3	1.10	48	1720	44	<5	<20	235	0.31	<10	115	<10	29	220
STSD3		0.5	5.56	25	1275	<5	2.45	2	18	40	48	4.33	1.39	30	1.27	2574	7	1.25	36	1690	52	5	<20	240	0.38	<10	126	<10	30	214


ICP: 4 ACID DIGEST/ICP-FINISH

AG: 4 ACID DIGEST/AA-FINISH



metallurgical assay

E.T. No.	Tag.No.	PT Values (g/t)		
		+140 mesh	- 140 mesh	total
1965-1	S07-05443	0.01	0.01	0.01
1965-2	S07-05444	0.01	0.01	0.01
1965-3	S07-05445	0.01	0.01	0.01
1965-4	S07-05446	0.01	0.01	0.01
1965-5	S07-05447	0.01	0.01	0.01
1965-6	S07-05448	0.01	0.01	0.01
1965-7	S07-05449	0.01	0.01	0.01
1965-8	S07-05450	0.01	0.01	0.01
1965-9	S07-05451	0.01	0.01	0.01
1965-10	S07-05452	0.01	0.01	0.01
1965-12	S07-05454	0.01	0.01	0.01
1965-13	S07-05455	0.01	0.01	0.01
1965-14	S07-05456	0.01	0.01	0.01
1965-15	S07-05457	0.02	0.01	0.01
1965-16	S07-05458	0.01	0.01	0.01
1965-18	S07-05460	0.01	0.01	0.01
1965-19	S07-05461	0.03	0.01	0.01
1965-20	S07-05462	0.03	0.03	0.03
1965-21	S07-05463	0.04	0.03	0.03
1965-22	S07-05464	0.02	0.03	0.03
1965-23	S07-05465	0.04	0.08	0.08
1965-24	S07-05466	0.01	0.02	0.02
1965-25	S07-05467	0.01	0.03	0.03
1965-26	S07-05468	0.01	0.01	0.01
1965-27	S07-05469	67.03	0.14	1.56
1965-29	S07-05471	0.01	0.01	0.01
1965-30	S07-05472	0.01	0.01	0.01
1965-31	S07-05473	0.01	0.01	0.01
1965-32	S07-05474	0.01	0.01	0.01
1965-33	S07-05475	0.06	0.01	0.01
1965-34	S07-05476	0.01	0.01	0.01
1965-35	S07-05477	0.03	0.01	0.01
1965-36	S07-05478	0.01	0.01	0.01
1965-37	S07-05479	0.01	0.01	0.01
1965-38	S07-05480	0.01	0.01	0.01
1965-39	S07-05481	0.01	0.01	0.01
1965-40	S07-05482	0.01	0.01	0.01
1965-41	S07-05483	0.02	0.01	0.01
1965-42	S07-05484	0.01	0.01	0.01
1965-43	S07-05485	0.01	0.01	0.01
1965-44	S07-05486	0.01	0.01	0.01
1965-45	S07-05487	0.01	0.01	0.01
1965-46	S07-05488	0.01	0.01	0.01
1965-47	S07-05489	0.01	0.01	0.01
1965-48	S07-05490	0.01	0.01	0.01
1965-49	S07-05491	0.01	0.01	0.01
R/S 1	S07-05443	0.01	0.01	0.01
R/S 36	S07-05478	0.01	0.01	0.01



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 1964

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

12-Dec-07

Attention: Bob Singh

No. of samples received: 100

Sample Type: Core

Project: Spanish Mountain


Shipment #: SMC-07-147

Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-05492	<0.03	<0.001
2	S07-05493	0.38	0.011
3	S07-05494	* 0.43	0.013
4	S07-05495	<0.03	<0.001
5	S07-05496	<0.03	<0.001
6	S07-05497	0.04	0.001
7	S07-05498	<0.03	<0.001
8	S07-05499	<0.03	<0.001
9	S07-05500	<0.03	<0.001
10	S07-05501	<0.03	<0.001
11	S07-05502	<0.03	<0.001
12	S07-05503	<0.03	<0.001
13	S07-05504	<0.03	<0.001
14	S07-05505	<0.03	<0.001
15	S07-05506	<0.03	<0.001
16	S07-05507	<0.03	<0.001
17	S07-05508	<0.03	<0.001
18	S07-05509	<0.03	<0.001
19	S07-05510	<0.03	<0.001
20	S07-05511	<0.03	<0.001
21	S07-05512	<0.03	<0.001
22	S07-05513	<0.03	<0.001
23	S07-05514	<0.03	<0.001
24	S07-05515	<0.03	<0.001
25	S07-05516	<0.03	<0.001
26	S07-05517	* 6.67	0.195
27	S07-05518	0.04	0.001
28	S07-05519	0.03	0.001
29	S07-05520	<0.03	<0.001

* = 30g FA


ECOTECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	S07-05521	<0.03	<0.001
31	S07-05522	<0.03	<0.001
32	S07-05523	<0.03	<0.001
33	S07-05524	<0.03	<0.001
34	S07-05525	<0.03	<0.001
35	S07-05526	<0.03	<0.001
36	S07-05527	<0.03	<0.001
37	S07-05528	0.28	0.008
38	S07-05529	0.17	0.005
39	S07-05530	0.15	0.004
40	S07-05531	0.17	0.005
41	S07-05532	0.12	0.003
42	S07-05533	0.22	0.006
43	S07-05534	0.17	0.005
44	S07-05535	0.15	0.004
45	S07-05536	0.20	0.006
46	S07-05537	0.25	0.007
47	S07-05538	0.28	0.008
48	S07-05539	0.22	0.006
49	S07-05540	0.19	0.005
50	S07-05541	0.18	0.005
51	S07-05542	0.21	0.006
52	S07-05543	8.28	0.241
53	S07-05544	0.21	0.006
54	S07-05545	0.23	0.007
55	S07-05546	0.15	0.004
56	S07-05547	0.15	0.004
57	S07-05548	0.31	0.009
58	S07-05549	1.10	0.032
59	S07-05550	<0.03	<0.001
60	S07-05551	0.72	0.021
61	S07-05552	1.11	0.032
62	S07-05553	0.67	0.019
63	S07-05554	1.38	0.040
64	S07-05555	3.17	0.092
65	S07-05556	0.93	0.027
66	S07-05557	1.09	0.032
67	S07-05558	1.22	0.036
68	S07-05559	2.07	0.060
69	S07-05560	0.76	0.022
70	S07-05561	0.81	0.024
71	S07-05562	0.26	0.008
72	S07-05563	0.23	0.007

* = 30g FA



ECO TECH LABORATORY LTD.

 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays


ET #.	Tag #	Au (g/t)	Au (oz/t)
73	S07-05564	0.81	0.024
74	S07-05565	0.58	0.017
75	S07-05566	0.09	0.002
76	S07-05567	0.07	0.002
77	S07-05568	0.25	0.007
78	S07-05569	0.73	0.021
79	S07-05570	0.28	0.008
80	S07-05571	0.35	0.010
81	S07-05572	0.24	0.007
82	S07-05573	0.57	0.017
83	S07-05574	0.42	0.012
84	S07-05575	0.38	0.011
85	S07-05576	0.05	0.001
86	S07-05577	0.38	0.011
87	S07-05578	0.31	0.009
88	S07-05579	0.17	0.005
89	S07-05580	0.53	0.015
90	S07-05581	0.97	0.028
91	S07-05582	0.36	0.010
92	S07-05583	<0.03	<0.001
93	S07-05584	0.28	0.008
94	S07-05585	0.74	0.022
95	S07-05586	0.13	0.004
96	S07-05587	0.06	0.002
97	S07-05588	<0.03	<0.001
98	S07-05589	0.05	0.001
99	S07-05590	0.10	0.003
100	S07-05591	0.09	0.003

QC DATA:

Resplit:

1	S07-05492	<0.03	<0.001
36	S07-05527	<0.03	<0.001
71	S07-05562	0.40	0.012

* = 30g FA



ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
Standard:			
	OXi54	1.86	0.054
	OXi54	1.88	0.055
	OXi54	1.90	0.055
	OXi54	1.86	0.054
	OXi54	1.90	0.055
	OXi54	1.90	0.055
	OXi54		

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA
JJ/nl
XLS/07



ECO TECH LABORATORY LTD.
Julia Jealouse
B.C. Certified Assayer

ECO TECH LABORATORY LTD.

10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2007-1964

Skygold Ventures
615 - 800 W. Pender Street
Vancouver, BC
V6B 2V6

No. of samples received: 100
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-147
Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-05492	<0.2	3.88	440	445	5	4.09	3	42	939	13	4.01	1.19	<10	6.12	2206	<1	0.29	394	340	20	15	<20	183	0.07	<10	61	<10	6	62
2	S07-05493	<0.2	3.50	285	400	10	4.21	2	34	587	16	3.88	1.25	<10	5.61	1651	<1	0.21	246	340	20	15	<20	258	0.05	<10	76	<10	6	48
3	S07-05494	0.9	5.93	200	205	<5	0.28	1	7	29	32	3.25	4.36	<10	0.29	197	3	0.10	12	390	18	40	<20	30	0.38	<10	64	<10	10	50
4	S07-05495	0.2	2.84	450	140	5	5.14	3	43	835	18	3.75	1.05	<10	7.39	1192	<1	0.26	434	310	14	15	<20	278	0.03	<10	70	<10	5	36
5	S07-05496	0.5	3.47	440	155	<5	4.18	3	50	851	58	4.59	1.10	<10	7.94	1313	<1	0.28	444	390	16	25	<20	199	0.03	<10	91	<10	5	40
6	S07-05497	<0.2	4.34	155	760	<5	2.29	1	18	305	15	2.85	1.23	10	4.02	1018	<1	0.17	113	250	18	5	<20	152	0.06	<10	39	<10	6	35
7	S07-05498	0.2	4.57	125	830	<5	1.16	<1	17	305	20	2.62	1.27	20	3.12	599	<1	0.15	103	250	24	10	<20	69	0.08	<10	33	<10	7	37
8	S07-05499	<0.2	4.48	135	240	10	1.83	<1	25	454	4	4.24	1.26	<10	6.78	975	<1	0.22	221	390	16	10	<20	88	0.06	<10	60	<10	6	59
9	S07-05500	0.2	3.51	425	115	5	4.19	3	52	963	120	4.51	1.08	<10	7.78	1267	<1	0.24	519	400	18	20	<20	145	0.03	<10	81	<10	4	43
10	S07-05501	0.2	3.78	355	100	10	4.53	2	60	922	51	4.96	0.81	<10	8.20	1239	<1	0.19	520	440	16	15	<20	147	0.02	<10	84	<10	4	43
11	S07-05502	0.2	3.51	295	105	10	4.11	2	43	722	64	4.35	1.09	<10	6.64	1332	<1	0.20	374	430	14	10	<20	157	0.04	<10	82	<10	6	36
12	S07-05503	0.2	5.10	85	245	<5	1.64	<1	16	259	73	2.92	1.29	10	3.60	693	<1	0.71	92	360	18	5	<20	99	0.08	<10	39	<10	5	32
13	S07-05504	0.5	5.23	25	145	<5	1.21	<1	14	264	124	2.84	0.99	10	3.49	518	<1	1.59	85	390	20	5	<20	90	0.09	<10	39	<10	6	33
14	S07-05505	<0.2	4.11	80	45	5	3.29	<1	35	547	31	3.94	0.80	<10	6.71	1060	<1	0.31	265	400	16	10	<20	124	0.04	<10	66	<10	7	49
15	S07-05506	<0.2	4.83	150	215	<5	2.28	<1	19	379	11	3.26	1.29	<10	4.85	889	<1	0.47	200	310	18	5	<20	130	0.06	<10	51	<10	6	50
16	S07-05507	<0.2	4.86	90	180	<5	2.10	<1	25	279	60	4.24	1.49	<10	6.13	978	<1	0.38	131	460	18	5	<20	83	0.07	<10	83	<10	6	43
17	S07-05508	0.5	3.40	230	155	10	4.31	1	44	682	83	4.64	1.13	<10	7.88	1375	<1	0.20	408	430	16	20	<20	191	0.03	<10	86	<10	5	42
18	S07-05509	<0.2	3.42	315	180	<5	4.37	2	45	676	79	4.75	1.19	<10	7.77	1450	<1	0.21	420	410	16	15	<20	205	0.03	<10	87	<10	5	38
19	S07-05510	<0.2	3.22	135	100	<5	4.54	<1	39	621	58	4.44	0.85	<10	8.09	1320	<1	0.17	296	450	16	10	<20	151	0.03	<10	90	<10	6	37
20	S07-05511	0.2	2.49	230	125	5	4.50	1	43	707	48	3.95	0.93	<10	6.91	1229	<1	0.11	424	260	14	15	<20	175	0.02	<10	60	<10	4	31
21	S07-05512	<0.2	4.30	175	365	5	2.80	1	21	371	4	2.86	1.33	10	4.48	990	<1	0.25	176	270	16	10	<20	101	0.05	<10	39	<10	8	31
22	S07-05513	0.3	4.94	10	660	<5	0.34	<1	4	63	16	1.11	1.55	20	1.21	246	<1	0.71	9	190	22	<5	<20	35	0.09	<10	16	<10	5	18
23	S07-05514	0.2	4.98	20	775	<5	0.47	<1	6	63	41	1.26	1.43	20	1.13	346	<1	0.85	18	190	22	<5	<20	41	0.08	<10	15	<10	5	20
24	S07-05515	<0.2	4.33	125	260	<5	2.29	<1	28	478	38	3.41	1.05	10	5.34	878	<1	0.35	241	400	16	10	<20	81	0.06	<10	48	<10	6	42
25	S07-05516	<0.2	3.41	90	50	<5	5.00	<1	44	817	86	4.81	0.26	<10	8.40	1250	<1	0.22	449	430	14	10	<20	144	0.03	<10	87	<10	5	41
26	S07-05517	6.3	3.83	315	265	<5	0.41	2	6	38	53	3.70	2.99	<10	0.27	240	6	0.49	19	300	18	65	<20	73	0.22	<10	37	<10	7	56
27	S07-05518	<0.2	4.05	125	210	10	2.86	<1	31	505	34	4.09	1.04	10	5.78	1039	<1	0.24	254	490	16	10	<20	90	0.05	<10	59	<10	6	42
28	S07-05519	<0.2	4.67	20	815	<5	0.92	<1	6	127	58	1.63	1.43	20	1.44	393	<1	0.13	24	180	16	<5	<20	56	0.09	<10	17	<10	5	14
29	S07-05520	<0.2	4.82	15	815	<5	0.89	<1	4	102	25	1.24	1.37	20	0.99	516	<1	0.12	10	160	20	<5	<20	54	0.08	<10	14	<10	5	16
30	S07-05521	<0.2	3.93	10	700	<5	1.20	1	3	171	15	1.01	1.34	20	0.84	598	<1	0.10	10	120	20	<5	<20	75	0.07	<10	16	<10	6	93

Et #.	Ta	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	W	Y	Zn		
31	S07-05522	<0.2	4.27	10	780	<5	0.54	<1	3	96	28	1.16	1.26	20	0.85	463	<1	0.23	8	140	16	<5	<20	39	0.07	<10	11	<10	4	21
32	S07-05523	0.2	4.45	30	730	<5	0.93	<1	5	109	18	1.78	1.25	20	1.60	801	<1	0.16	22	190	16	<5	<20	58	0.08	<10	15	<10	5	37
33	S07-05524	<0.2	4.38	290	245	5	1.63	2	34	584	5	3.73	1.08	10	5.43	775	<1	0.26	232	360	14	10	<20	98	0.06	<10	54	<10	4	108
34	S07-05525	<0.2	0.98	<5	60	<5	>10	<1	<1	4	2	0.16	0.09	<10	1.62	98	<1	0.03	22	50	8	<5	<20	3759	<0.01	<10	1	<10	<1	2
35	S07-05526	<0.2	4.02	460	160	10	3.19	3	50	992	80	4.64	1.12	<10	6.10	1376	<1	0.29	435	460	20	15	<20	140	0.04	<10	88	<10	4	85
36	S07-05527	<0.2	4.38	300	260	<5	3.78	2	31	517	35	4.24	1.31	<10	5.13	1588	<1	0.23	235	320	18	10	<20	191	0.05	<10	66	<10	6	107
37	S07-05528	1.3	5.91	70	440	5	2.76	<1	28	324	147	6.25	2.10	20	1.83	1040	36	0.16	115	450	34	5	<20	169	0.08	<10	219	<10	9	36
38	S07-05529	0.9	4.23	55	275	10	2.08	<1	18	219	134	3.75	1.93	20	1.23	740	30	0.08	63	580	36	5	<20	110	0.07	<10	185	<10	7	40
39	S07-05530	1.5	4.73	75	340	5	2.45	2	21	216	72	4.90	1.95	20	1.30	908	33	0.10	80	760	36	10	<20	104	0.07	<10	195	<10	6	126
40	S07-05531	2.4	4.22	55	275	10	1.95	3	17	200	75	4.18	1.83	20	1.06	739	28	0.10	63	670	32	15	<20	74	0.07	<10	168	<10	5	184
41	S07-05532	1.3	4.09	45	255	10	2.03	2	16	180	56	3.24	1.52	20	1.12	855	18	0.08	52	500	26	10	<20	72	0.08	<10	128	<10	5	119
42	S07-05533	3.1	5.08	45	310	5	2.49	3	19	228	78	4.75	2.11	20	1.24	873	34	0.11	73	810	42	15	<20	90	0.09	<10	202	<10	6	173
43	S07-05534	2.2	3.98	25	230	5	2.80	1	16	268	81	3.81	1.32	20	1.35	967	24	0.08	61	560	30	20	<20	93	0.07	<10	147	<10	6	104
44	S07-05535	1.8	4.01	20	180	5	2.77	2	17	269	76	3.91	1.63	20	1.46	1056	26	0.07	67	680	36	15	<20	107	0.08	<10	171	<10	6	153
45	S07-05536	2.9	4.30	55	245	<5	2.58	3	16	267	106	4.45	1.75	20	1.38	1035	30	0.12	68	700	36	15	<20	91	0.07	<10	176	<10	5	171
46	S07-05537	3.0	4.17	30	250	5	1.99	3	16	272	90	4.31	1.86	20	1.24	773	30	0.11	64	700	36	15	<20	79	0.08	<10	184	<10	5	168
47	S07-05538	3.5	3.89	45	210	<5	2.12	2	15	233	86	3.97	1.77	20	1.25	896	28	0.12	58	670	36	15	<20	82	0.08	<10	180	<10	6	151
48	S07-05539	2.4	3.79	20	255	5	2.14	2	14	259	83	3.81	1.87	20	1.29	838	25	0.09	59	750	32	15	<20	86	0.07	<10	180	<10	6	142
49	S07-05540	2.1	4.53	35	230	<5	2.52	3	16	196	69	4.08	1.93	10	1.39	1066	27	0.10	63	660	36	15	<20	85	0.07	<10	183	<10	5	180
50	S07-05541	2.2	4.47	20	340	<5	2.23	2	16	200	73	3.98	2.04	20	1.24	845	27	0.10	64	650	38	15	<20	76	0.07	<10	195	<10	5	179
51	S07-05542	2.1	4.61	20	140	<5	2.08	3	16	260	69	4.19	2.12	20	1.21	847	28	0.16	64	700	38	15	<20	79	0.07	<10	203	<10	5	186
52	S07-05543	3.3	2.86	15	245	<5	1.34	11	10	271	64	2.84	1.45	10	0.84	551	24	0.07	48	380	222	15	<20	61	0.05	<10	169	<10	3	820
53	S07-05544	2.5	3.93	40	280	<5	2.19	2	14	238	55	3.70	1.58	10	1.06	707	26	0.08	56	610	36	15	<20	79	0.05	<10	167	<10	4	113
54	S07-05545	2.8	4.42	40	255	10	2.49	3	16	264	63	4.27	1.98	20	1.33	821	29	0.10	68	700	42	15	<20	110	0.07	<10	205	<10	6	205
55	S07-05546	0.2	5.56	40	200	<5	2.61	2	12	248	76	3.43	1.63	20	1.63	821	19	0.31	34	660	26	5	<20	112	0.11	<10	164	<10	6	109
56	S07-05547	0.4	6.55	70	295	<5	1.88	<1	15	195	81	4.04	1.59	10	1.95	695	3	1.01	19	690	28	<5	<20	105	0.12	<10	121	<10	6	73
57	S07-05548	0.2	6.00	40	230	<5	2.13	2	11	261	69	3.07	1.81	20	1.57	778	5	0.54	24	510	30	5	<20	114	0.11	<10	144	<10	5	133
58	S07-05549	0.6	5.49	55	140	<5	2.92	2	14	138	145	3.36	1.69	20	1.38	643	7	0.32	28	600	36	<5	<20	110	0.11	<10	145	<10	5	109
59	S07-05550	<0.2	1.24	<5	60	<5	>10	<1	<1	45	21	0.30	0.12	<10	1.48	100	<1	0.10	24	90	8	<5	<20	3688	0.01	<10	2	<10	1	6
60	S07-05551	0.3	4.69	55	315	<5	3.86	3	11	127	113	3.03	1.20	10	1.52	1039	8	0.68	23	900	24	<5	<20	148	0.10	<10	172	<10	5	191
61	S07-05552	0.5	6.46	100	375	<5	3.80	4	14	304	108	4.01	1.45	20	1.53	728	12	0.35	30	850	34	5	<20	125	0.17	<10	213	<10	7	274
62	S07-05553	0.7	7.33	45	435	<5	3.69	1	18	93	146	4.75	1.85	10	2.38	630	<1	1.05	14	690	36	<5	<20	160	0.15	<10	170	<10	8	94
63	S07-05554	0.8	6.18	105	330	<5	3.59	2	21	239	119	4.22	2.44	20	1.51	731	65	0.49	57	760	88	5	<20	125	0.15	<10	358	<10	6	117
64	S07-05555	1.1	5.87	60	225	<5	3.15	3	15	236	141	3.71	1.72	20	1.32	613	17	0.88	42	870	28	<5	<20	107	0.15	<10	277	<10	6	190
65	S07-05556	0.5	5.39	35	255	<5	4.06	1	10	158	102	3.78	1.29	20	1.57	800	11	0.68	21	900	26	<5	<20	114	0.13	<10	150	<10	8	113
66	S07-05557	0.4	5.25	65	155	<5	2.54	2	11	151	126	3.17	1.50	20	1.10	605	11	0.52	30	680	18	<5	<20	89	0.10	<10	171	<10	5	131
67	S07-05558	0.5	5.17	15	185	<5	4.30	1	16	166	82	4.03	0.81	20	1.49	1029	8	0.71	26	1110	26	<5	<20	139	0.11	<10	133	<10	6	95
68	S07-05559	4.8	4.65	165	290	<5	0.45	2	11	32	588	4.92	2.35	10	1.66	336	6	0.27	19	370	72	40	<20	59	0.21	<10	42	<10	10	657
69	S07-05560	0.8	6.33	65	105	<5	2.76	1	20	153	75	4.55	1.98	20	1.13	673	23	0.71	36	760	42	5	<20	88	0.13	<10	224	<10	5	108
70	S07-05561	1.1	4.38	15	125	<5	1.77	<1	11	156	69	3.20	1.87	10	0.97	406	12	0.49	25	430	28	5	<20	70	0.09	<10	165	<10	4	68

Et #.	Ta	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	W	Y	Zn		
71	S07-05562	0.8	5.45	15	165	<5	2.12	<1	9	118	66	3.07	1.75	20	0.98	432	9	0.74	23	430	28	<5	<20	73	0.09	<10	106	<10	6	68
72	S07-05563	0.4	5.16	25	135	<5	1.97	<1	9	113	41	2.92	1.30	20	0.92	407	8	0.50	20	390	22	<5	<20	63	0.09	<10	98	<10	5	50
73	S07-05564	0.9	5.63	55	115	<5	1.87	2	11	90	64	2.58	1.43	20	0.91	374	9	0.65	21	420	24	<5	<20	60	0.10	<10	107	<10	5	94
74	S07-05565	0.7	4.73	20	220	<5	1.50	1	7	51	97	1.85	1.70	10	0.75	323	8	0.63	18	360	20	<5	<20	55	0.08	<10	102	<10	4	91
75	S07-05566	0.3	4.85	40	225	<5	2.39	2	7	174	65	2.05	1.10	20	1.00	649	9	0.31	16	420	20	<5	<20	82	0.07	<10	78	<10	4	145
76	S07-05567	0.4	5.02	35	280	<5	2.17	9	5	220	67	1.77	1.03	10	1.02	594	7	0.16	14	490	30	<5	<20	93	0.08	<10	81	<10	6	605
77	S07-05568	0.3	6.59	25	320	<5	3.13	<1	6	143	73	2.39	1.39	20	1.54	631	4	0.44	9	440	26	<5	<20	104	0.11	<10	67	<10	11	44
78	S07-05569	0.7	7.07	60	145	<5	2.96	<1	13	120	80	3.39	2.39	20	1.25	690	2	0.74	17	620	30	<5	<20	90	0.13	<10	99	<10	5	61
79	S07-05570	<0.2	6.72	30	135	<5	2.78	<1	14	149	81	3.33	1.98	20	1.27	646	2	0.77	16	550	28	<5	<20	90	0.13	<10	106	<10	5	45
80	S07-05571	0.3	6.88	30	230	<5	3.59	<1	13	117	56	3.59	2.12	10	1.51	861	<1	1.07	11	530	24	<5	<20	120	0.11	<10	96	<10	6	32
81	S07-05572	<0.2	6.10	50	265	<5	4.00	<1	10	144	56	2.84	1.23	20	1.62	851	1	0.96	11	560	26	<5	<20	159	0.11	<10	77	<10	8	66
82	S07-05573	<0.2	5.89	20	310	<5	3.06	<1	10	173	49	2.38	1.14	10	1.35	619	1	0.91	10	380	24	<5	<20	137	0.12	<10	63	<10	8	48
83	S07-05574	0.2	6.13	25	655	<5	2.83	<1	7	98	43	1.88	1.19	10	1.30	606	3	0.85	8	450	30	<5	<20	132	0.12	<10	67	<10	7	41
84	S07-05575	0.3	6.10	40	230	<5	3.10	<1	8	72	51	2.34	1.13	20	1.43	650	2	0.63	10	370	26	<5	<20	129	0.11	<10	60	<10	7	49
85	S07-05576	0.2	4.48	40	245	<5	2.61	1	11	131	46	2.13	1.05	20	1.11	667	1	0.67	25	350	26	<5	<20	107	0.11	<10	79	<10	5	130
86	S07-05577	1.0	4.71	120	205	<5	1.95	4	18	304	66	5.81	1.78	10	0.90	737	54	0.17	46	750	64	5	<20	111	0.09	<10	239	<10	5	297
87	S07-05578	0.8	5.58	60	425	<5	4.15	1	18	201	113	4.34	2.34	<10	1.89	1257	7	0.24	29	510	48	5	<20	142	0.12	<10	167	<10	5	118
88	S07-05579	0.5	6.16	60	290	<5	3.18	<1	11	188	113	2.53	1.61	10	1.46	992	22	0.48	29	590	32	<5	<20	120	0.14	<10	174	<10	5	70
89	S07-05580	1.1	7.18	85	590	<5	4.34	1	16	225	162	3.81	2.88	10	1.95	1140	6	0.35	32	820	44	<5	<20	159	0.17	<10	128	<10	9	89
90	S07-05581	0.9	6.44	20	705	<5	3.00	<1	7	236	68	2.84	1.88	10	1.46	896	3	0.25	13	620	30	<5	<20	118	0.17	<10	85	<10	7	74
91	S07-05582	0.2	6.38	20	550	<5	3.24	<1	6	160	37	2.95	1.52	20	1.37	982	12	0.24	10	760	34	<5	<20	158	0.15	<10	68	<10	8	72
92	S07-05583	<0.2	0.93	<5	55	<5	>10	<1	<1	5	12	0.19	0.08	<10	1.45	79	<1	0.05	19	70	8	<5	<20	4178	<0.01	<10	2	<10	<1	4
93	S07-05584	0.5	7.70	75	220	<5	2.96	<1	11	81	156	3.80	2.03	30	1.13	933	46	0.35	9	710	46	<5	<20	170	0.16	<10	55	<10	7	83
94	S07-05585	7.5	7.56	55	255	<5	3.22	18	14	142	395	3.85	3.04	20	1.37	1133	28	0.35	19	690	1338	<5	<20	198	0.19	<10	104	<10	8	1489
95	S07-05586	0.5	7.33	30	725	<5	3.36	<1	15	134	146	4.31	1.34	10	1.64	1175	4	1.24	26	620	34	<5	<20	213	0.17	<10	178	<10	5	116
96	S07-05587	<0.2	7.15	35	715	<5	2.64	<1	15	170	39	4.13	1.39	20	1.65	1211	1	1.50	19	710	26	<5	<20	194	0.19	<10	114	<10	6	81
97	S07-05588	0.3	6.85	30	670	<5	2.29	<1	15	76	76	4.08	1.53	20	1.59	1055	<1	1.57	19	640	24	<5	<20	189	0.19	<10	116	<10	5	97
98	S07-05589	<0.2	7.38	40	615	<5	3.27	<1	19	100	99	4.35	1.42	10	1.97	1247	<1	1.51	24	720	30	<5	<20	217	0.21	<10	135	<10	6	91
99	S07-05590	0.2	7.50	55	280	<5	3.56	<1	26	90	160	5.33	1.31	10	1.83	1322	1	1.45	26	620	34	<5	<20	222	0.17	<10	205	<10	4	85
100	S07-05591	0.3	7.07	10	780	<5	3.83	<1	19	91	63	4.54	1.26	10	1.95	1518	<1	1.37	18	750	38	<5	<20	244	0.18	<10	193	<10	4	74


QC DATA:**Repeat:**

1	S07-05492	<0.2	3.76	400	400	<5	3.62	3	40	804	14	4.10	1.27	<10	5.87	1960	<1	0.29	360	310	20	15	<20	166	0.05	<10	58	<10	6	55
10	S07-05501	<0.2	3.69	370	105	15	4.49	2	57	915	51	4.85	0.78	<10	8.24	1256	<1	0.20	523	430	16	15	<20	147	0.02	<10	79	<10	4	43
19	S07-05510	<0.2	3.24	125	100	5	4.63	<1	40	615	56	4.61	0.81	<10	7.93	1367	<1	0.17	305	460	14	10	<20	148	0.03	<10	92	<10	6	37
36	S07-05527	<0.2	4.36	295	270	<5	3.71	2	32	511	35	4.36	1.28	<10	5.37	1675	<1	0.23	245	330	20	10	<20	202	0.05	<10	70	<10	7	111
45	S07-05536	2.8	4.56	45	270	10	2.75	2	15	257	105	4.31	1.87	20	1.34	988	29	0.10	64	670	38	15	<20	88	0.08	<10	177	<10	5	160
54	S07-05545	2.8	4.66	60	245	10	2.79	3	18	269	69	4.46	2.05	20	1.39	825	33	0.12	77	790	48	15	<20	114	0.08	<10	209	<10	6	223
71	S07-05562	0.8	5.38	20	145	5	1.98	1	9	121	68	3.06	1.82	20	0.94	403	9	0.74	22	410	28	<5	<20	70	0.08	<10	104	<10	6	67
80	S07-05571	0.5	7.04	40	245	<5	3.79	<1	17	122	60	3.36	2.35	10	1.71	901	1	0.97	12	540	30	<5	<20	127	0.16	<10	98	<10	6	40
89	S07-05580	1.0	7.18	70	540	<5	4.17	<1	15	206	151	3.71	2.24	10	1.84	1075	6	0.33	29	790	40	<5	<20	155	0.17	<10	126	<10	9	90


Et #.	T.	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	W	Y	Zn		
Resplit:																														
1	S07-05492	0.2	3.58	380	455	5	3.83	2	30	956	10	3.92	1.05	<10	5.90	2066	<1	0.25	277	300	18	10	<20	157	0.05	<10	56	<10	5	55
36	S07-05527	<0.2	4.57	285	275	<5	3.76	2	35	529	39	4.46	0.95	<10	5.29	1533	<1	0.24	243	320	20	10	<20	186	0.05	<10	70	<10	7	110
71	S07-05562	0.7	5.95	15	175	<5	2.06	<1	12	110	60	3.12	1.91	20	1.05	433	10	0.65	25	470	30	5	<20	81	0.10	<10	117	<10	6	70
Standard:																														
STSD3		0.5	5.71	25	1295	<5	2.24	<1	14	51	37	4.14	1.32	30	1.11	2488	5	1.13	27	1690	42	<5	<20	250	0.29	<10	110	<10	23	205
STSD3		0.4	5.52	25	1270	<5	2.16	<1	14	53	37	4.20	1.31	30	1.13	2499	5	1.22	28	1640	44	<5	<20	245	0.30	<10	104	<10	26	203
STSD3		0.5	5.60	25	1350	<5	2.33	1	17	63	43	4.29	1.39	40	1.33	2517	7	1.15	32	1710	50	5	<20	268	0.35	<10	124	<10	30	211

ICP: 4 ACID DIGEST/ICP-FINISH
 AG: 4 ACID DIGEST/AA-FINISH

JJ/nl
 df/td1964S
 XLS/07



ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 1936

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

3-Dec-07


Attention: Bob Singh

No. of samples received: 111
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-149
Samples submitted by: Tasha Gainer

Metallic Assays


ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-05592	0.13	0.004
2	S07-05593	0.15	0.004
3	S07-05594	* 0.40	0.012
4	S07-05595	<0.03	<0.001
5	S07-05596	<0.03	<0.001
6	S07-05597	<0.03	<0.001
7	S07-05598	0.25	0.007
8	S07-05599	0.18	0.005
9	S07-05600	<0.03	<0.001
10	S07-05601	0.03	0.001
11	S07-05602	0.05	0.001
12	S07-05603	0.07	0.002
13	S07-05604	0.14	0.004
14	S07-05605	0.12	0.004
15	S07-05606	0.65	0.019
16	S07-05607	0.23	0.007
17	S07-05608	0.23	0.007
18	S07-05609	0.09	0.003
19	S07-05610	<0.03	<0.001
20	S07-05611	<0.03	<0.001
21	S07-05612	0.14	0.004
22	S07-05613	0.13	0.004
23	S07-05614	0.08	0.002
24	S07-05615	<0.03	<0.001
25	S07-05616	0.12	0.004
26	S07-05617	0.04	0.001
27	S07-05618	0.03	0.001
28	S07-05619	* <0.03	<0.001
29	S07-05620	<0.03	<0.001
30	S07-05621	<0.03	<0.001

* = 30 FA


ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

		Metallic Assays	
ET #.	Tag #	Au (g/t)	Au (oz/t)
31	S07-05622	<0.03	<0.001
32	S07-05623	0.04	0.001
33	S07-05624	0.06	0.002
34	S07-05625	<0.03	<0.001
35	S07-05626	<0.03	<0.001
36	S07-05627	<0.03	<0.001
37	S07-05628	<0.03	<0.001
38	S07-05629	<0.03	<0.001
39	S07-05630	*	6.66 0.194
40	S07-05631	0.16	0.005
41	S07-05632	0.05	0.001
42	S07-05633	<0.03	<0.001
43	S07-05634	<0.03	<0.001
44	S07-05635	<0.03	<0.001
45	S07-05636	<0.03	<0.001
46	S07-05637	<0.03	<0.001
47	S07-05638	<0.03	<0.001
48	S07-05639	<0.03	<0.001
49	S07-05640	<0.03	<0.001
50	S07-05641	0.03	0.001
51	S07-05642	0.03	0.001
52	S07-05643	<0.03	<0.001
53	S07-05644	0.11	0.003
54	S07-05645	0.04	0.001
55	S07-05646	<0.03	<0.001
56	S07-05647	0.03	0.001
57	S07-05648	<0.03	<0.001
58	S07-05649	0.03	0.001
59	S07-05650	0.03	0.001
60	S07-05651	0.03	0.001
61	S07-05652	*	<0.03 <0.001
62	S07-05653	<0.03	<0.001
63	S07-05654	<0.03	<0.001
64	S07-05655	<0.03	<0.001
65	S07-05656	<0.03	<0.001
66	S07-05657	<0.03	<0.001
67	S07-05658	0.03	0.001
68	S07-05659	<0.03	<0.001
69	S07-05660	<0.03	<0.001
70	S07-05661	0.06	0.002
71	S07-05662	0.04	0.001
72	S07-05663	*	2.08 0.061
73	S07-05664	0.74	0.022

* = 30 FA



ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer


Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
74	S07-05665	<0.03	<0.001
75	S07-05666	<0.03	<0.001
76	S07-05667	1.34	0.039
77	S07-05668	0.03	0.001
78	S07-05669	<0.03	<0.001
79	S07-05670	0.05	0.001
80	S07-05671	<0.03	<0.001
81	S07-05672	0.06	0.002
82	S07-05673	0.80	0.023
83	S07-05674	1.97	0.057
84	S07-05675	1.25	0.037
85	S07-05676	0.31	0.009
86	S07-05677	0.22	0.006
87	S07-05678	0.10	0.003
88	S07-05679	0.06	0.002
89	S07-05680	0.06	0.002
90	S07-05681	0.05	0.001
91	S07-05682	0.14	0.004
92	S07-05683	0.05	0.001
93	S07-05684	0.05	0.001
94	S07-05685	<0.03	<0.001
95	S07-05686	* <0.03	<0.001
96	S07-05687	0.10	0.003
97	S07-05688	<0.03	<0.001
98	S07-05689	<0.03	<0.001
99	S07-05690	0.05	0.001
100	S07-05691	0.11	0.003
101	S07-05692	<0.03	<0.001
102	S07-05693	0.04	0.001
103	S07-05694	<0.03	<0.001
104	S07-05695	<0.03	<0.001
105	S07-05696	<0.03	<0.001
106	S07-05697	* 0.42	0.012
107	S07-05698	<0.03	<0.001
108	S07-05699	0.05	0.002
109	S07-05700	0.08	0.002
110	S07-05701	<0.03	<0.001
111	S07-05702	0.06	0.002

QC DATA:Resplit:

1	S07-05592	0.15	0.004
---	-----------	------	-------

* = 30 FA



ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
36	S07-05627	<0.03	<0.001
71	S07-05662	0.04	0.001
107	S07-05698	<0.03	<0.001

Standard:

OXK48	3.56	0.104
OXK48	3.54	0.103
OXK48	3.54	0.103
OXK48	3.54	0.103
OXK48	3.58	0.104
OXK48	3.58	0.104
OXK48	3.57	0.104
OXK48	3.54	0.103
OXK48	3.52	0.103

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

U/nl

LS/07



ECO TECH LABORATORY LTD.

Jutta Jealous

B.C. Certified Assayer

ECO TEC. LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE ANALYSIS AK 2007-1936

Skygold Ventures
615 - 800 W. Pender Street
Vancouver, BC
V6B 2V6

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 111
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-149
Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y
1	S07-05592	<0.2	5.85	30	460	<5	2.70	1	19	68	107	4.22	1.93	10	1.59	1201	<1	1.24	20	800	72	<5	<20	216	0.18	<10	156	<10	5
2	S07-05593	<0.2	7.68	40	605	10	3.35	1	23	88	93	5.15	1.85	10	1.77	1210	<1	0.97	24	670	54	<5	<20	300	0.21	<10	197	<10	6
3	S07-05594	0.8	4.38	115	180	<5	0.23	2	7	26	39	2.81	2.76	10	0.26	151	4	0.17	11	620	18	40	<20	46	0.38	<10	80	<10	11
4	S07-05595	<0.2	9.93	30	775	<5	4.87	<1	23	120	65	6.80	2.36	10	1.78	1256	<1	1.65	22	1150	40	5	<20	390	0.25	<10	236	<10	5
5	S07-05596	<0.2	8.96	35	695	<5	4.25	<1	17	116	59	5.39	2.20	10	1.55	900	<1	2.08	15	730	28	<5	<20	377	0.21	<10	176	<10	6
6	S07-05597	<0.2	7.22	20	455	<5	2.79	<1	11	145	72	4.32	1.62	10	1.30	700	<1	2.68	13	810	24	<5	<20	270	0.23	<10	131	<10	6
7	S07-05598	<0.2	7.69	25	695	<5	4.57	<1	15	65	95	4.95	2.24	10	1.85	1127	<1	1.36	15	1060	26	<5	<20	355	0.22	<10	182	<10	7
8	S07-05599	<0.2	7.74	25	805	<5	3.13	<1	16	95	96	5.32	2.32	10	1.64	830	<1	1.42	16	800	30	<5	<20	279	0.22	<10	206	<10	5
9	S07-05600	<0.2	7.69	20	570	<5	2.93	<1	13	74	57	4.52	2.16	20	1.32	734	<1	2.24	11	1020	22	<5	<20	302	0.22	<10	135	<10	6
10	S07-05601	<0.2	7.64	20	655	<5	3.42	<1	15	47	111	5.03	2.43	10	1.60	856	<1	2.11	18	760	28	<5	<20	267	0.21	<10	198	<10	4
11	S07-05602	<0.2	7.55	25	795	<5	2.52	<1	16	69	104	4.64	2.48	10	1.45	712	<1	2.06	19	830	28	<5	<20	235	0.18	<10	202	<10	4
12	S07-05603	<0.2	9.42	25	1000	<5	4.41	<1	21	58	41	5.77	2.76	10	1.81	1098	<1	1.51	17	930	32	<5	<20	342	0.25	<10	230	<10	5
13	S07-05604	0.2	7.99	15	740	<5	3.53	<1	13	56	156	4.85	2.40	20	1.18	859	<1	1.37	8	1210	38	<5	<20	324	0.28	<10	159	<10	9
14	S07-05605	0.6	8.10	15	530	10	3.70	<1	21	36	331	7.34	2.04	20	1.65	1107	1	1.67	10	1800	38	<5	<20	338	0.32	<10	276	<10	12
15	S07-05606	1.6	8.38	35	670	<5	4.98	<1	21	56	350	7.46	2.04	20	1.57	1124	1	1.33	11	1770	38	<5	<20	437	0.32	<10	255	<10	11
16	S07-05607	0.9	7.72	20	570	<5	3.57	<1	19	66	302	6.80	2.70	20	1.55	1017	<1	1.88	8	1780	34	<5	<20	307	0.28	<10	251	<10	11
17	S07-05608	0.6	8.29	25	560	<5	3.77	<1	22	117	271	7.33	2.21	20	1.48	1052	<1	1.80	10	1910	32	<5	<20	303	0.31	<10	248	<10	11
18	S07-05609	0.4	7.95	20	565	<5	4.44	<1	17	126	167	6.67	2.50	20	1.63	1131	2	0.98	10	2180	30	<5	<20	286	0.34	<10	244	<10	12
19	S07-05610	<0.2	6.63	15	745	<5	2.64	<1	10	277	61	4.11	2.54	20	1.35	804	<1	0.96	12	760	22	5	<20	207	0.21	<10	144	<10	6
20	S07-05611	<0.2	7.27	15	945	<5	2.89	<1	13	80	80	4.61	2.67	20	1.66	855	<1	1.98	12	750	22	<5	<20	274	0.22	<10	178	<10	5
21	S07-05612	0.2	7.61	25	880	<5	3.48	<1	16	116	90	5.61	2.03	20	1.59	966	<1	1.17	12	1080	30	<5	<20	264	0.24	<10	175	<10	6
22	S07-05613	<0.2	7.33	20	710	<5	3.08	<1	11	161	53	4.55	2.47	10	1.24	926	<1	1.27	11	840	28	<5	<20	243	0.22	<10	144	<10	5
23	S07-05614	<0.2	7.74	20	735	<5	2.70	<1	15	134	101	5.16	2.39	<10	1.41	920	<1	1.51	12	740	26	<5	<20	279	0.23	<10	169	<10	5
24	S07-05615	0.2	8.03	20	590	<5	2.70	<1	17	94	62	5.50	2.03	<10	1.49	992	<1	2.65	12	800	28	<5	<20	308	0.27	<10	179	<10	4
25	S07-05616	0.2	9.38	25	710	<5	3.40	<1	20	106	90	6.52	2.24	<10	1.47	1068	<1	2.59	15	990	28	<5	<20	367	0.30	<10	208	<10	4

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	S07-05617	0.2	7.86	20	680	<5	2.83	<1	18	75	130	5.84	2.09	<10	1.53	1000	<1	2.57	13	630	28	<5	<20	363	0.25	<10	211	<10	3	78
27	S07-05618	0.6	7.51	25	350	<5	2.48	<1	19	105	119	5.17	1.14	<10	1.52	822	<1	3.65	18	680	24	<5	<20	372	0.22	<10	165	<10	4	76
28	S07-05619	<0.2	1.33	<5	70	<5	>10	<1	<1	3	14	0.26	0.12	<10	1.77	94	<1	0.09	29	80	6	<5	<20	4950	<0.01	<10	5	<10	1	8
29	S07-05620	<0.2	7.63	45	665	<5	4.31	1	28	188	46	6.21	2.11	10	2.73	1185	<1	2.05	42	1060	22	<5	<20	445	0.19	<10	249	<10	6	81
30	S07-05621	<0.2	7.34	45	1070	10	5.26	<1	26	141	113	6.07	2.40	<10	3.02	1209	<1	1.60	41	1300	22	<5	<20	455	0.18	<10	236	<10	7	53
31	S07-05622	<0.2	7.81	45	845	<5	5.11	<1	27	137	77	6.81	1.93	<10	3.10	1249	<1	2.00	44	920	24	<5	<20	673	0.20	<10	245	<10	6	74
32	S07-05623	<0.2	8.42	35	675	<5	4.61	<1	26	75	142	6.66	2.39	<10	2.44	1159	<1	1.48	24	840	26	<5	<20	401	0.23	<10	266	<10	5	68
33	S07-05624	0.2	7.52	25	595	<5	4.15	<1	22	51	132	6.13	1.82	<10	2.24	1105	<1	2.51	19	910	26	<5	<20	537	0.25	<10	244	<10	5	53
34	S07-05625	0.4	7.90	20	725	<5	2.84	<1	23	57	95	5.74	2.00	10	1.92	917	<1	2.69	21	810	26	<5	<20	338	0.28	<10	220	<10	5	62
35	S07-05626	<0.2	7.72	20	610	<5	2.29	<1	20	47	89	5.06	1.12	10	1.69	780	5	3.53	18	850	26	<5	<20	352	0.27	<10	179	<10	6	79
36	S07-05627	0.2	7.45	15	575	<5	2.40	<1	16	49	95	5.07	0.79	10	1.75	886	<1	3.80	17	910	22	<5	<20	349	0.30	<10	175	<10	5	73
37	S07-05628	<0.2	8.52	45	2435	<5	4.65	<1	31	129	157	6.74	2.35	10	2.91	1288	<1	1.55	53	1010	24	<5	<20	444	0.25	<10	303	<10	8	88
38	S07-05629	0.2	8.74	35	1030	<5	3.86	<1	25	88	120	6.92	1.26	10	2.56	1046	<1	2.72	37	1210	24	<5	<20	371	0.35	<10	291	<10	9	102
39	S07-05630	5.8	3.98	190	160	<5	0.39	2	7	46	77	3.62	2.97	<10	0.25	235	9	0.50	20	440	22	70	<20	87	0.33	<10	61	<10	10	60
40	S07-05631	0.2	8.48	45	845	<5	4.13	<1	24	79	110	6.12	1.18	10	2.14	1178	1	4.13	32	1280	34	<5	<20	426	0.35	<10	238	<10	9	75
41	S07-05632	<0.2	8.89	25	625	<5	4.95	<1	21	80	179	6.18	0.90	20	2.17	1171	4	4.03	28	1550	50	<5	<20	399	0.36	<10	231	<10	11	74
42	S07-05633	<0.2	8.54	30	335	<5	3.85	<1	29	203	121	6.79	0.60	10	3.25	1158	2	3.38	56	1260	30	5	<20	336	0.27	<10	294	<10	10	99
43	S07-05634	<0.2	8.39	35	285	<5	3.85	<1	35	233	192	7.26	0.44	10	3.99	1217	<1	2.94	73	1250	26	<5	<20	347	0.18	<10	270	<10	8	95
44	S07-05635	<0.2	8.22	25	495	<5	4.52	<1	37	314	195	7.46	1.01	10	3.89	1268	1	2.92	90	1260	32	10	<20	409	0.22	<10	330	<10	9	80
45	S07-05636	0.2	8.26	35	370	20	3.85	<1	35	276	139	7.22	0.93	10	3.98	1128	<1	2.74	84	1170	26	5	<20	375	0.19	<10	236	<10	8	74
46	S07-05637	<0.2	7.30	70	400	5	4.62	<1	37	398	193	6.97	1.32	10	4.36	1218	<1	1.79	124	970	22	10	<20	406	0.13	<10	307	<10	8	76
47	S07-05638	<0.2	7.86	50	1635	<5	3.89	<1	26	201	113	6.31	2.17	10	3.72	1160	<1	1.39	53	1050	26	<5	<20	353	0.18	<10	248	<10	8	63
48	S07-05639	<0.2	8.67	30	1885	<5	4.81	<1	26	184	96	6.40	2.29	10	3.53	1380	<1	1.75	40	1080	28	<5	<20	450	0.21	<10	256	<10	9	60
49	S07-05640	0.4	9.69	30	1535	<5	4.12	<1	26	147	119	6.90	2.01	10	3.24	1352	<1	2.37	36	1240	36	<5	<20	404	0.25	<10	235	<10	9	75
50	S07-05641	<0.2	7.93	30	935	<5	4.32	<1	24	246	108	5.34	1.48	20	3.12	1244	<1	2.67	56	1280	24	5	<20	391	0.19	<10	203	<10	10	62
51	S07-05642	<0.2	7.86	30	885	<5	3.34	<1	24	289	115	5.74	1.56	20	3.30	1095	<1	2.47	59	1180	24	5	<20	364	0.21	<10	218	<10	11	73
52	S07-05643	0.2	8.57	25	1870	<5	3.24	<1	23	110	119	6.07	2.02	10	3.19	1312	<1	2.30	31	1110	26	<5	<20	338	0.23	<10	242	<10	7	69
53	S07-05644	<0.2	9.19	25	1525	<5	2.47	<1	21	135	101	6.53	1.46	20	2.22	1306	<1	2.79	23	1310	38	<5	<20	309	0.30	<10	187	<10	9	82
54	S07-05645	<0.2	8.68	20	1300	<5	1.83	<1	15	85	53	6.08	1.67	20	2.02	1177	<1	3.58	12	1320	30	<5	<20	294	0.33	<10	143	<10	8	89
55	S07-05646	<0.2	8.39	15	1210	<5	2.06	<1	19	89	82	6.70	1.23	20	2.36	1186	<1	3.01	15	1260	24	5	<20	328	0.34	<10	191	<10	8	97
56	S07-05647	<0.2	7.73	25	1860	<5	2.72	<1	20	98	113	6.27	1.54	10	2.30	1089	<1	2.39	24	1050	24	<5	<20	350	0.25	<10	224	<10	7	87
57	S07-05648	0.2	8.44	20	2360	<5	1.54	<1	20	137	101	5.78	2.04	10	2.08	986	<1	2.51	17	930	26	5	<20	236	0.27	<10	209	<10	5	92
58	S07-05649	<0.2	7.73	20	2705	<5	2.26	<1	20	94	81	6.08	1.71	10	2.17	1194	<1	2.68	19	1260	28	<5	<20	302	0.29	<10	222	<10	7	81
59	S07-05650	0.4	8.11	25	2465	<5	1.29	<1	17	124	96	6.07	1.66	20	2.20	1045	<1	2.81	14	1180	28	<5	<20	233	0.31	<10	161	<10	7	95
60	S07-05651	<0.2	8.12	40	4560	<5	2.26	<1	26	127	112	7.19	2.39	10	3.50	1573	<1	1.57	33	1140	24	<5	<20	272	0.24	<10	247	<10	5	102
61	S07-05652	<0.2	1.49	<5	65	<5	>10	<1	<1	2	12	0.29	0.14	<10	1.69	99	<1	0.09	24	120	<2	<5	<20	5100	<0.01	<10	3	<10	<1	6
62	S07-05653	0.2	7.88	50	2915	<5	2.71	<1	27	89	105	6.97	1.71	10	3.25	1513	<1	1.66	37	1000	24	<5	<20	322	0.22	<10	235	<10	5	84
63	S07-05654	<0.2	9.12	40	2475	<5	3.73	<1	26	83	123	7.11	2.05	10	3.29	1781	<1	2.44	34	1160	28	<5	<20	399	0.28	<10	269	<10	6	80
64	S07-05655	0.2	8.49	35	1855	<5	4.43	<1	24	84	125	6.58	2.07	10	3.33	1996	<1	2.60	33	1270	26	<5	<20	480	0.25	<10	238	<10	8	77
65	S07-05656	<0.2	8.12	20	1775	<5	2.12	<1	26	84	102	6.84	2.05	10	3.45	1495	<1	2.36	34	1030	22	<5	<20	285	0.24	<10	256	<10	5	82

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
66	S07-05657	0.2	8.07	20	1545	<5	1.93	<1	26	77	93	6.65	1.88	10	3.33	1543	<1	2.48	34	980	24	<5	<20	269	0.22	<10	235	<10	4	88
67	S07-05658	0.3	7.44	15	1760	<5	2.23	<1	24	76	93	6.24	2.16	10	3.14	1554	<1	2.05	32	980	22	<5	<20	285	0.23	<10	258	<10	5	87
68	S07-05659	0.4	8.22	25	1905	<5	1.96	<1	30	93	89	6.29	2.38	10	3.13	1421	<1	1.77	35	1030	28	<5	<20	268	0.21	<10	264	<10	5	74
69	S07-05660	0.7	7.48	20	1130	<5	2.26	<1	26	81	343	5.91	2.00	<10	2.83	1365	<1	2.12	32	850	24	<5	<20	300	0.19	<10	215	<10	5	84
70	S07-05661	<0.2	6.71	15	1430	<5	3.34	<1	20	80	92	5.00	1.91	<10	2.84	1354	<1	1.67	30	800	24	<5	<20	430	0.15	<10	234	<10	6	80
71	S07-05662	0.6	6.72	15	1135	<5	1.42	<1	17	69	147	5.02	1.62	20	2.10	767	3	0.26	45	890	26	<5	<20	162	0.18	<10	188	<10	6	168
72	S07-05663	4.7	4.70	90	135	<5	0.49	3	13	38	647	5.29	2.17	10	1.65	389	10	0.23	21	530	98	50	<20	68	0.31	<10	63	<10	12	658
73	S07-05664	0.9	6.24	40	240	5	1.23	2	15	52	96	4.42	2.50	10	1.68	652	5	0.21	40	410	40	<5	<20	133	0.16	<10	252	<10	5	288
74	S07-05665	0.2	6.96	15	2775	<5	1.63	<1	7	59	32	3.24	2.04	20	1.82	711	2	0.18	41	500	24	<5	<20	180	0.17	<10	125	<10	7	125
75	S07-05666	<0.2	6.16	20	2130	<5	1.19	<1	17	68	43	3.40	2.20	20	1.71	622	1	0.18	37	680	22	<5	<20	136	0.18	<10	117	<10	6	97
76	S07-05667	1.8	4.99	40	205	5	2.21	2	20	105	134	4.06	2.00	20	1.39	748	29	0.12	67	490	52	<5	<20	216	0.13	<10	135	<10	7	185
77	S07-05668	<0.2	6.76	15	2430	<5	1.33	1	10	58	53	2.98	2.34	20	1.57	645	2	0.18	27	390	24	<5	<20	142	0.17	<10	147	<10	6	183
78	S07-05669	<0.2	7.01	25	2135	<5	1.90	<1	11	73	34	3.78	1.95	20	2.05	817	2	0.26	26	570	24	<5	<20	229	0.15	<10	105	<10	9	73
79	S07-05670	0.6	6.66	20	220	<5	1.68	<1	22	92	132	5.68	1.86	20	2.04	748	8	0.23	37	1140	30	<5	<20	184	0.17	<10	194	<10	9	93
80	S07-05671	0.2	6.11	20	960	<5	1.10	1	15	87	112	4.19	2.16	10	1.71	707	4	0.22	62	480	26	<5	<20	131	0.16	<10	153	<10	5	177
81	S07-05672	0.2	7.81	45	185	<5	1.59	1	27	71	88	5.85	2.28	10	2.19	917	1	0.30	49	570	34	<5	<20	162	0.20	<10	200	<10	6	158
82	S07-05673	0.6	5.59	25	405	5	1.63	3	13	200	109	3.63	1.94	10	1.38	777	8	0.14	48	440	30	<5	<20	166	0.16	<10	290	<10	6	375
83	S07-05674	1.8	6.67	30	75	<5	1.89	2	30	110	168	6.27	2.09	20	1.93	970	8	0.23	51	850	58	<5	<20	184	0.18	<10	222	<10	7	284
84	S07-05675	1.0	7.13	40	145	<5	1.87	2	23	171	139	5.47	2.24	10	2.01	959	6	0.27	46	780	40	<5	<20	193	0.18	<10	228	<10	7	197
85	S07-05676	0.6	6.84	25	1340	<5	1.43	2	14	196	109	3.85	2.14	20	1.67	780	13	0.22	44	550	30	<5	<20	160	0.19	<10	238	<10	7	249
86	S07-05677	0.4	6.46	35	500	<5	2.35	2	12	203	103	4.11	1.60	20	1.95	1090	11	0.21	58	570	60	5	<20	260	0.18	<10	254	<10	8	208
87	S07-05678	0.4	5.31	40	705	<5	2.56	2	12	167	101	3.08	1.88	20	1.61	2082	17	0.21	109	580	30	<5	<20	266	0.19	<10	199	<10	9	233
88	S07-05679	0.5	5.68	70	965	<5	2.48	<1	15	202	114	3.15	1.94	20	1.89	2667	<1	0.35	111	420	30	<5	<20	287	0.18	<10	95	<10	7	142
89	S07-05680	<0.2	5.77	55	830	<5	5.69	<1	8	130	87	2.82	2.07	20	2.08	5215	<1	0.40	75	550	28	5	<20	571	0.14	<10	73	<10	10	139
90	S07-05681	0.4	5.92	50	1090	<5	3.99	<1	11	150	54	2.98	1.94	20	1.94	4903	<1	0.62	98	540	26	<5	<20	399	0.18	<10	88	<10	7	102
91	S07-05682	0.8	6.62	60	105	<5	1.05	<1	29	210	195	5.10	2.44	30	1.60	2094	1	0.76	158	520	36	<5	<20	137	0.21	<10	106	<10	5	173
92	S07-05683	0.8	6.30	100	1130	<5	1.04	1	19	180	166	3.82	2.04	30	1.78	2941	2	0.78	171	510	32	5	<20	141	0.22	<10	109	<10	5	194
93	S07-05684	0.8	7.10	100	1365	<5	1.62	<1	19	205	194	3.88	2.40	30	2.02	4666	<1	0.72	175	500	32	<5	<20	191	0.23	<10	120	<10	6	191
94	S07-05685	<0.2	6.76	65	1300	<5	1.03	<1	17	156	153	3.55	2.60	40	1.92	3371	1	0.72	196	570	36	5	<20	142	0.27	<10	121	<10	6	191
95	S07-05686	<0.2	1.12	<5	40	<5	>10	<1	<1	<1	12	0.12	0.04	<10	1.64	69	<1	0.04	29	50	4	<5	<20	5315	<0.01	<10	2	<10	<1	6
96	S07-05687	0.8	5.98	60	1060	<5	1.30	<1	20	196	177	3.78	2.12	30	1.78	4435	1	0.61	205	490	36	<5	<20	162	0.19	<10	108	<10	6	246
97	S07-05688	<0.2	6.79	75	1470	<5	0.88	<1	15	184	150	4.02	2.47	30	1.82	5164	1	0.75	143	530	34	5	<20	126	0.22	<10	115	<10	7	145
98	S07-05689	0.4	6.03	40	1150	<5	1.13	<1	14	182	161	3.64	2.35	20	1.71	5895	1	0.54	140	460	32	<5	<20	140	0.20	<10	113	<10	6	147
99	S07-05690	0.4	5.82	35	200	<5	1.12	<1	22	269	160	4.44	2.50	20	1.63	5153	1	0.52	113	420	38	5	<20	137	0.16	<10	106	<10	6	174
100	S07-05691	1.1	6.97	90	155	<5	1.67	1	28	228	245	5.36	2.14	30	1.74	5532	2	0.68	211	480	56	5	<20	185	0.19	<10	118	<10	7	275
101	S07-05692	0.4	6.36	55	960	<5	2.23	<1	20	199	126	4.05	1.62	30	1.81	7150	<1	0.61	153	500	34	<5	<20	242	0.21	<10	117	<10	8	154
102	S07-05693	0.2	6.39	35	1100	<5	1.39	1	22	175	166	4.02	2.28	20	1.71	5759	<1	0.72	154	440	32	<5	<20	160	0.22	<10	116	<10	6	315
103	S07-05694	0.8	6.46	40	1225	<5	1.29	1	21	145	165	3.63	2.55	30	1.83	5544	1	0.63	197	450	34	5	<20	154	0.22	<10	115	<10	6	232
104	S07-05695	0.4	6.84	30	1480	<5	1.17	<1	20	202	138	4.01	2.66	30	2.01	4771	<1	0.61	171	490	38	<5	<20	155	0.22	<10	123	<10	7	171
105	S07-05696	0.4	6.87	65	1215	<5	1.21	<1	17	244	118	3.84	2.00	30	1.83	3995	1	0.67	134	490	34	5	<20	160	0.22	<10	113	<10	7	140

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
106	S07-05697	0.8	4.99	140	115	<5	0.25	1	9	29	38	2.94	2.12	10	0.29	201	5	0.18	15	490	28	40	<20	47	0.41	<10	80	<10	11	56
107	S07-05698	<0.2	5.73	80	1005	<5	1.63	1	17	314	84	3.39	1.98	30	1.89	4119	1	0.50	162	480	48	5	<20	206	0.20	<10	100	<10	8	153
108	S07-05699	0.6	5.67	95	700	<5	1.43	1	20	260	107	3.56	1.79	20	1.82	3607	<1	0.44	125	510	30	5	<20	182	0.19	<10	96	<10	7	139
109	S07-05700	0.4	5.65	35	835	<5	0.80	<1	13	283	126	3.83	1.73	20	1.86	2546	<1	0.36	113	340	32	5	<20	125	0.19	<10	91	<10	6	135
110	S07-05701	0.7	4.12	70	585	<5	1.73	<1	17	298	88	2.56	1.48	10	1.59	2660	<1	0.24	88	400	26	5	<20	198	0.15	<10	77	<10	6	117
111	S07-05702	1.0	4.58	100	230	<5	1.62	1	26	384	151	4.00	1.55	20	1.62	2257	3	0.26	140	530	36	10	<20	194	0.13	<10	90	<10	8	168

QC DATA:

Repeat:

1	S07-05592	0.2	6.21	30	475	<5	2.62	1	17	72	105	4.77	2.07	10	1.73	1163	<1	1.45	19	770	78	<5	<20	222	0.17	<10	174	<10	5	104
10	S07-05601	<0.2	7.86	25	675	<5	3.63	<1	17	52	115	5.28	2.27	10	1.68	915	<1	2.33	19	790	26	<5	<20	273	0.21	<10	200	<10	4	81
19	S07-05610	<0.2	6.94	10	735	<5	2.83	<1	11	264	57	4.36	2.41	20	1.36	853	<1	0.96	13	810	18	5	<20	204	0.22	<10	140	<10	6	53
36	S07-05627	<0.2	8.15	20	580	<5	2.57	<1	17	47	84	5.13	0.84	10	1.72	913	<1	3.78	18	950	26	<5	<20	356	0.32	<10	169	<10	6	74
45	S07-05636	0.4	8.07	40	360	15	3.70	<1	33	284	141	7.34	0.96	10	3.93	1072	<1	2.77	81	1180	28	5	<20	381	0.19	<10	251	<10	8	73
54	S07-05645	<0.2	8.41	15	1285	<5	1.77	<1	14	83	53	5.90	1.67	20	1.99	1160	<1	3.42	13	1260	28	<5	<20	292	0.34	<10	141	<10	9	88
71	S07-05662	0.4	6.52	20	1045	<5	1.37	<1	23	79	150	4.95	1.85	20	2.16	775	3	0.27	47	880	28	<5	<20	164	0.17	<10	175	<10	6	146
80	S07-05671	0.3	6.40	25	900	<5	1.17	1	16	92	117	4.30	2.18	10	1.84	744	5	0.25	62	490	26	<5	<20	137	0.16	<10	157	<10	5	177
89	S07-05680	<0.2	5.43	25	840	<5	5.27	<1	7	133	94	2.63	2.18	20	2.12	5005	<1	0.39	74	540	24	<5	<20	593	0.13	<10	78	<10	11	136

Resplit:


1	S07-05592	<0.2	6.03	35	440	<5	2.57	1	19	62	113	4.87	1.83	10	1.69	1350	<1	1.35	22	780	68	<5	<20	224	0.18	<10	143	<10	4	152
36	S07-05627	<0.2	7.73	20	565	<5	2.46	<1	20	49	71	5.27	0.91	10	1.75	869	<1	3.90	19	870	26	5	<20	349	0.28	<10	182	<10	5	76
71	S07-05662	0.4	6.69	20	1445	<5	1.49	<1	21	71	148	4.55	1.64	20	2.07	758	3	0.29	50	990	26	<5	<20	171	0.18	<10	183	<10	7	134
107	S07-05698	<0.2	5.98	90	1080	<5	1.66	1	16	194	84	3.36	1.97	30	1.89	4207	<1	0.54	154	500	58	5	<20	207	0.19	<10	99	<10	7	147


Standard:

STSD3	0.4	5.93	25	1355	<5	2.48	1	16	63	44	4.23	1.44	40	1.31	2473	7	1.21	30	1760	54	5	<20	294	0.37	<10	123	<10	34	215
STSD3	0.5	5.69	25	1280	<5	2.51	1	17	61	42	4.28	1.57	40	1.26	2544	8	1.15	31	1760	62	5	<20	286	0.37	<10	128	<10	32	211
STSD3	0.5	5.77	25	1440	<5	2.69	1	17	64	45	4.35	1.42	40	1.37	2574	7	1.25	33	1700	58	5	<20	294	0.37	<10	131	<10	30	220
STSD3	0.4	5.77	25	1385	<5	2.45	1	17	62	42	4.14	1.39	30	1.29	2531	6	1.14	32	1630	56	5	<20	261	0.34	<10	118	<10	32	206

ICP: 4 ACID DIGEST/ICP-FINISH
 AG: 4 ACID DIGEST/AA-FINISH

JJ/jl
 dt/td1936
 XLS/07


 ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2279

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

4-Mar-08


Attention: Bob Singh

No. of samples received: 81
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-150
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-34275	<0.03	<0.001
2	S07-34276	<0.03	<0.001
3	S07-34277	<0.03	<0.001
4	S07-34278	* 0.44	0.013
5	S07-34279	<0.03	<0.001
6	S07-34280	<0.03	<0.001
7	S07-34281	<0.03	<0.001
8	S07-34282	<0.03	<0.001
9	S07-34283	<0.03	<0.001
10	S07-34284	<0.03	<0.001
11	S07-34285	<0.03	<0.001
12	S07-34286	<0.03	<0.001
13	S07-34287	<0.03	<0.001
14	S07-34288	<0.03	<0.001
15	S07-34289	<0.03	<0.001
16	S07-34290	<0.03	<0.001
17	S07-34291	<0.03	<0.001
18	S07-34292	<0.03	<0.001
19	S07-34293	<0.03	<0.001
20	S07-34294	<0.03	<0.001
21	S07-34295	<0.03	<0.001
22	S07-34296	<0.03	<0.001
23	S07-34297	<0.03	<0.001
24	S07-34298	* <0.03	<0.001
25	S07-34299	<0.03	<0.001
26	S07-34300	<0.03	<0.001
27	S07-34301	<0.03	<0.001
28	S07-34302	<0.03	<0.001
29	S07-34303	<0.03	<0.001
30	S07-34304	<0.03	<0.001


* = 30g FA


ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
31	S07-34305	<0.03	<0.001
32	S07-34306	<0.03	<0.001
33	S07-34307	<0.03	<0.001
34	S07-34308	<0.03	<0.001
35	S07-34309	<0.03	<0.001
36	S07-34310	* 6.62	0.193
37	S07-34311	<0.03	<0.001
38	S07-34312	0.11	0.003
39	S07-34313	0.15	0.004
40	S07-34314	0.20	0.006
41	S07-34315	0.17	0.005
42	S07-34316	0.20	0.006
43	S07-34317	0.13	0.004
44	S07-34318	0.11	0.003
45	S07-34319	0.15	0.004
46	S07-34320	0.12	0.004
47	S07-34321	0.20	0.006
48	S07-34322	2.26	0.066
49	S07-34323	0.22	0.006
50	S07-34324	<0.03	<0.001
51	S07-34325	0.04	0.001
52	S07-34326	0.26	0.008
53	S07-34327	0.13	0.004
54	S07-34328	1.57	0.046
55	S07-34329	1.60	0.047
56	S07-34330	1.50	0.044
57	S07-34331	3.39	0.099
58	S07-34332	1.48	0.043
59	S07-34333	0.20	0.006
60	S07-34334	6.41	0.187
61	S07-34335	0.70	0.020
62	S07-34336	* <0.03	<0.001
63	S07-34337	0.62	0.018
64	S07-34338	7.22	0.210
65	S07-34339	1.59	0.046
66	S07-34340	0.11	0.003
67	S07-34341	<0.03	<0.001
68	S07-34342	1.32	0.039
69	S07-34343	8.38	0.244
70	S07-34344	* 6.66	0.194
71	S07-34345	0.36	0.011
72	S07-34346	0.15	0.004
73	S07-34347	1.30	0.038

* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jelouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
74	S07-34348	1.64	0.048
75	S07-34349	3.60	0.105
76	S07-34350	0.43	0.013
77	S07-34351	0.17	0.005
78	S07-34352	0.64	0.019
79	S07-34353	1.20	0.035
80	S07-34354	<0.03	<0.001
81	S07-34355	0.03	0.001

QC DATA:

Resplit:

1	S07-34275	<0.03	<0.001
37	S07-34311	<0.03	<0.001
71	S07-34345	0.43	0.012

Standard:

OXK48	3.56	0.104
OXK48	3.58	0.104
OXK48	3.52	0.103
OXK48	3.56	0.104
OXK48	3.57	0.104
OXK48	3.59	0.105
OXK48	3.60	0.105


1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw
XLS/07

ECO TECH LABORATORY LTD.

Jutta Jealous
B.C. Certified Assayer



TECH LABORATORY LTD.

Dallas Drive
 OOPS, B.C.
 ST4

ICP CERTIFICATE OF ANALYSIS 2007-2279

Skygold Ventures
 615 - 800 W. Pender Street
 Vancouver, BC
 V6B 2V6

250-573-5700
 250-573-4557

No. of samples received: 81
 Sample Type: Core
 Project: Spanish Mountain
 Shipment #: SMC-07-150
 Samples submitted by: Tasha Gainer


Values in ppm unless otherwise reported


Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
S07-34275	0.8	6.54	15	800	<5	1.12	<1	4	35	39	1.93	2.63	10	1.03	1736	<1	0.77	12	420	42	<5	<20	83	0.15	<10	30	<10	6	60
S07-34276	0.4	5.02	10	600	<5	1.10	<1	3	53	25	1.64	2.10	10	0.95	1410	2	0.57	9	380	28	<5	<20	87	0.11	<10	30	<10	4	30
S07-34277	0.4	5.89	10	650	<5	1.00	<1	4	83	23	1.86	2.56	10	1.35	940	<1	0.38	15	290	30	<5	<20	70	0.12	<10	25	<10	5	43
S07-34278	1.0	5.86	95	200	<5	0.27	<1	8	24	30	3.45	4.44	10	0.33	163	3	0.12	15	500	20	40	<20	52	0.37	<10	68	<10	11	44
S07-34279	0.2	5.66	15	560	<5	1.45	<1	7	96	11	2.46	2.47	10	1.89	1560	<1	0.28	37	280	44	<5	<20	88	0.11	<10	34	<10	7	94
S07-34280	0.4	4.89	80	305	<5	2.61	<1	31	684	3	4.42	1.76	<10	4.84	2658	<1	0.55	296	390	24	10	<20	163	0.05	<10	64	<10	4	108
S07-34281	0.2	5.14	10	580	<5	1.65	<1	5	99	11	2.00	2.36	10	2.19	1408	<1	0.25	26	260	24	<5	<20	93	0.11	<10	29	<10	6	35
S07-34282	0.6	5.37	90	555	<5	1.13	<1	18	322	43	3.44	2.42	10	2.04	1314	1	0.26	126	410	28	5	<20	85	0.10	<10	58	<10	6	80
S07-34283	0.8	5.93	110	490	<5	1.20	<1	28	588	101	4.64	2.51	20	3.01	1863	9	0.32	166	680	34	10	<20	96	0.11	<10	160	<10	6	102
S07-34284	0.4	4.68	160	225	<5	2.32	<1	45	984	27	5.42	1.99	<10	5.53	2021	6	0.37	355	600	38	10	<20	179	0.08	<10	135	<10	4	164
S07-34285	0.4	4.01	150	210	<5	2.39	<1	26	706	14	4.54	1.82	10	4.15	1475	4	0.19	204	480	42	10	<20	163	0.07	<10	97	<10	4	175
S07-34286	0.2	4.63	80	195	<5	3.23	<1	32	633	7	4.42	1.79	10	5.04	1515	<1	0.54	225	520	24	10	<20	171	0.06	<10	99	<10	5	115
S07-34287	0.4	2.83	20	115	<5	3.29	<1	14	287	9	2.88	1.05	20	3.52	1152	<1	0.28	67	1400	18	5	<20	195	0.06	<10	94	<10	8	47
S07-34288	0.2	3.18	30	120	<5	2.72	<1	24	328	5	3.46	1.12	10	3.97	956	2	0.35	89	1420	20	5	<20	164	0.07	<10	107	<10	7	65
S07-34289	0.2	3.20	40	175	10	4.46	<1	18	319	9	3.04	1.26	20	3.54	1543	2	0.26	110	1060	20	5	<20	238	0.06	<10	93	<10	8	47
S07-34290	0.2	3.56	105	130	<5	5.47	<1	14	331	9	3.63	1.18	10	4.63	2121	2	0.54	116	410	22	5	<20	288	0.05	<10	89	<10	6	78
S07-34291	0.6	4.83	85	285	<5	2.89	<1	25	377	81	4.38	2.02	10	4.38	1234	<1	0.46	136	850	30	5	<20	171	0.10	<10	138	<10	6	85
S07-34292	0.8	5.00	55	260	<5	2.16	<1	26	421	98	3.95	1.73	10	3.05	985	<1	0.73	125	540	36	5	<20	138	0.09	<10	105	<10	5	86
S07-34293	0.4	4.86	390	315	<5	5.40	<1	50	919	78	5.36	2.02	<10	3.71	2205	2	0.39	362	650	28	15	<20	256	0.06	<10	133	<10	5	191
S07-34294	0.4	6.28	35	135	<5	2.38	<1	25	303	72	4.83	1.26	20	4.52	926	<1	2.14	99	600	28	5	<20	206	0.12	<10	147	<10	5	80
S07-34295	0.4	6.38	30	155	<5	1.40	<1	23	172	100	4.50	1.02	20	2.06	737	<1	3.41	56	470	30	<5	<20	166	0.13	<10	104	<10	6	43
S07-34296	1.0	5.97	20	135	<5	2.26	<1	17	218	196	4.12	0.68	20	1.55	937	1	3.34	49	620	26	<5	<20	191	0.14	<10	88	<10	9	26
S07-34297	1.0	5.96	20	175	<5	2.05	<1	19	104	148	3.91	0.75	20	1.43	784	<1	3.09	53	600	30	<5	<20	187	0.12	<10	86	<10	7	34
S07-34298	0.2	7.23	10	575	<5	2.65	<1	10	50	36	4.29	1.07	10	1.31	779	4	3.00	28	810	32	<5	<20	316	0.37	<10	110	<10	17	47
S07-34299	0.6	6.18	40	115	<5	1.87	<1	23	226	117	4.88	1.32	20	1.74	734	1	1.79	74	560	26	<5	<20	155	0.13	<10	104	<10	9	75

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
S07-34300	0.6	5.63	100	235	<5	4.21	<1	44	805	113	5.89	1.82	10	4.91	1174	1	0.74	246	690	28	10	<20	231	0.09	<10	134	<10	6	153
S07-34301	0.8	5.43	85	260	<5	3.98	<1	30	1019	109	5.02	1.69	10	3.86	1091	3	1.56	188	530	28	15	<20	250	0.10	<10	120	<10	6	128
S07-34302	0.6	5.38	30	130	<5	2.26	<1	21	648	139	5.01	1.75	20	2.43	809	3	1.00	75	610	28	10	<20	153	0.12	<10	93	<10	6	88
S07-34303	0.6	5.45	15	265	<5	1.75	<1	19	404	159	4.26	1.96	20	2.94	824	<1	1.18	62	570	26	5	<20	149	0.13	<10	99	<10	5	61
S07-34304	0.4	5.34	25	155	<5	0.68	<1	16	112	131	3.33	0.86	20	1.33	327	<1	3.63	42	560	24	<5	<20	130	0.12	<10	89	<10	4	24
S07-34305	0.2	3.92	50	125	<5	2.91	<1	26	493	14	3.93	1.25	<10	5.13	1141	2	0.57	174	520	18	5	<20	211	0.05	<10	95	<10	4	97
S07-34306	0.6	4.52	60	115	<5	3.12	<1	48	821	135	5.08	1.33	<10	6.51	1281	<1	0.73	340	680	22	15	<20	217	0.05	<10	131	<10	4	122
S07-34307	0.2	3.96	60	150	<5	4.80	<1	38	509	38	4.85	1.18	10	5.63	1458	<1	0.64	206	570	18	5	<20	285	0.06	<10	133	<10	6	101
S07-34308	0.2	4.92	50	225	<5	4.35	<1	30	421	53	4.35	1.70	10	4.36	1402	<1	0.91	160	850	24	5	<20	252	0.08	<10	125	<10	6	74
S07-34309	0.4	4.46	60	210	<5	4.81	<1	35	622	81	5.16	1.80	<10	5.11	1452	<1	0.46	221	680	24	10	<20	217	0.08	<10	144	<10	5	132
S07-34310	5.8	4.19	115	260	<5	0.39	<1	6	36	53	3.65	3.01	<10	0.27	218	6	0.54	19	380	26	60	<20	94	0.25	<10	48	<10	9	40
S07-34311	0.6	4.43	25	145	<5	4.45	1	20	458	70	4.43	2.03	20	2.31	1056	18	0.17	98	830	24	10	<20	192	0.07	<10	185	<10	7	109
S07-34312	1.0	4.74	20	170	<5	2.56	3	13	153	97	4.55	2.28	20	1.31	604	21	0.15	66	710	32	5	<20	133	0.06	<10	224	<10	7	210
S07-34313	1.0	5.16	20	140	<5	2.88	3	15	154	69	4.53	2.49	20	1.42	759	26	0.17	67	850	38	10	<20	162	0.07	<10	250	<10	6	177
S07-34314	1.4	3.35	15	140	<5	2.56	3	12	562	71	4.10	1.61	20	1.22	666	19	0.06	56	870	42	15	<20	164	0.07	<10	195	<10	7	157
S07-34315	1.6	4.16	15	120	<5	2.40	2	13	189	80	3.86	2.48	20	1.56	538	19	0.26	58	620	42	10	<20	192	0.05	<10	264	<10	8	118
S07-34316	2.0	4.47	15	130	<5	2.51	2	15	459	72	4.88	2.17	20	1.28	681	25	0.10	68	750	48	15	<20	159	0.08	<10	234	<10	8	147
S07-34317	1.4	4.48	15	185	<5	2.38	2	14	249	63	4.34	2.18	20	1.18	632	30	0.11	59	820	42	10	<20	137	0.07	<10	231	<10	7	144
S07-34318	1.0	4.50	15	170	<5	2.66	2	13	486	62	4.60	2.17	20	1.27	713	28	0.12	62	850	38	10	<20	153	0.08	<10	227	<10	7	161
S07-34319	1.4	4.83	15	95	<5	2.82	2	14	109	86	4.83	2.44	20	1.39	717	25	0.15	64	760	40	10	<20	149	0.06	<10	236	<10	6	161
S07-34320	1.4	4.41	15	160	<5	2.73	2	15	287	70	4.41	2.08	20	1.26	710	22	0.12	60	880	36	5	<20	145	0.06	<10	211	<10	6	133
S07-34321	1.0	5.44	15	80	<5	2.51	2	15	268	72	4.77	2.44	20	1.04	576	28	0.29	48	2070	30	5	<20	136	0.09	<10	167	<10	9	109
S07-34322	1.4	5.92	15	105	<5	2.64	2	17	134	145	5.59	2.65	20	1.33	507	24	0.46	57	620	34	<5	<20	154	0.08	<10	277	<10	6	138
S07-34323	0.2	7.15	10	835	<5	1.91	<1	10	104	84	3.54	2.77	10	1.72	437	5	1.25	18	610	32	<5	<20	142	0.10	<10	141	<10	6	63
S07-34324	<0.2	5.99	10	745	<5	2.04	<1	8	129	48	2.77	2.40	20	1.55	455	3	1.51	14	510	24	<5	<20	131	0.07	<10	113	<10	5	61
S07-34325	1.8	5.82	10	615	5	2.00	<1	9	88	48	3.11	2.35	10	1.53	423	2	1.36	14	500	24	<5	<20	125	0.07	<10	109	<10	4	49
S07-34326	0.2	6.11	10	790	<5	1.87	1	9	128	89	2.99	2.86	20	1.39	369	8	1.28	32	620	24	<5	<20	117	0.09	<10	213	<10	5	109
S07-34327	0.2	7.88	10	910	<5	1.08	2	8	129	120	3.86	3.01	20	1.51	287	18	1.35	34	730	30	<5	<20	82	0.12	<10	246	<10	5	144
S07-34328	0.8	6.32	20	255	<5	2.15	1	15	124	84	4.09	2.19	20	1.56	537	2	1.25	39	880	32	<5	<20	145	0.12	<10	143	<10	5	127
S07-34329	0.2	6.21	15	145	<5	2.73	<1	14	116	116	3.85	2.13	20	1.40	712	<1	1.10	35	860	34	<5	<20	176	0.13	<10	115	<10	6	67
S07-34330	1.0	7.37	45	170	<5	3.56	1	20	146	118	4.83	2.29	20	1.45	593	16	0.99	46	960	42	<5	<20	176	0.12	<10	159	<10	7	118
S07-34331	0.8	4.27	20	145	<5	2.21	<1	14	193	70	4.28	1.74	20	0.97	439	35	0.26	55	850	32	<5	<20	119	0.08	<10	187	<10	4	93
S07-34332	0.4	4.97	15	155	<5	4.16	2	12	147	79	4.18	1.94	20	1.55	726	13	0.60	34	1380	28	<5	<20	190	0.10	<10	223	<10	6	221
S07-34333	0.2	5.79	30	155	<5	6.18	1	16	94	77	5.55	2.23	20	2.24	1251	9	0.91	30	1670	32	<5	<20	276	0.09	<10	194	<10	8	150
S07-34334	1.8	7.10	55	100	<5	4.08	4	22	103	107	5.98	2.42	20	1.53	667	20	1.08	51	1260	46	<5	<20	182	0.13	<10	414	<10	8	409
S07-34335	0.4	>10	35	270	<5	6.38	5	22	148	106	6.95	1.98	10	1.85	1213	22	0.81	68	1320	50	<5	<20	204	0.20	<10	489	<10	7	456
S07-34336	<0.2	0.04	<5	5	<5	>10	<1	<1	1	53	0.03	<0.01	<10	1.68	22	<1	<0.01	32	50	6	<5	<20	6144	<0.01	<10	2	<10	<1	5
S07-34337	0.4	6.79	15	235	<5	3.67	4	11	155	103	4.01	2.19	20	1.43	713	13	1.27	36	770	28	<5	<20	176	0.11	<10	332	<10	5	316
S07-34338	1.4	5.88	20	105	<5	3.32	<1	16	86	75	4.36	1.93	20	1.26	627	7	1.32	32	720	28	<5	<20	166	0.09	<10	157	<10	5	107
S07-34339	0.8	6.63	25	560	<5	3.59	<1	11	84	51	3.23	2.12	20	1.44	720	1	1.17	28	660	32	<5	<20	172	0.13	<10	106	<10	7	71

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Li	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
S07-34340	0.2	6.96	30	290	<5	4.01	<1	11	54	33	3.65	2.18	20	1.72	929	<1	1.20	13	630	26	<5	<20	208	0.09	<10	89	<10	7	44
S07-34341	0.2	6.61	15	945	<5	2.51	<1	8	47	31	2.61	2.40	20	1.60	514	3	1.54	12	550	26	<5	<20	179	0.10	<10	74	<10	7	53
S07-34342	0.4	7.04	40	140	<5	5.18	<1	23	68	80	5.68	2.16	20	2.01	1232	7	1.40	32	910	38	<5	<20	232	0.12	<10	170	<10	7	84
S07-34343	0.6	5.77	30	135	<5	3.10	1	32	146	86	6.46	2.12	10	1.24	820	32	1.02	67	940	44	<5	<20	143	0.09	<10	287	<10	5	161
S07-34344	6.0	3.98	130	240	<5	0.43	<1	7	44	51	3.63	3.10	<10	0.26	248	6	0.49	23	410	22	65	<20	90	0.28	<10	54	<10	9	53
S07-34345	0.4	6.96	25	1060	<5	3.10	<1	9	62	61	2.80	2.38	20	1.46	704	6	0.82	20	770	35	<5	<20	150	0.17	<10	115	<10	8	96
S07-34346	0.4	6.25	15	1125	<5	3.29	<1	6	60	36	2.25	2.21	20	1.38	795	4	1.03	11	900	30	<5	<20	160	0.13	<10	86	<10	8	64
S07-34347	0.4	7.29	20	200	<5	2.77	<1	10	83	53	3.33	2.57	20	1.04	596	8	1.44	16	680	32	<5	<20	165	0.12	<10	95	<10	8	83
S07-34348	0.4	7.03	20	210	<5	3.27	<1	11	85	75	4.16	2.44	20	1.26	748	43	0.99	16	810	36	<5	<20	179	0.13	<10	127	<10	7	73
S07-34349	0.8	6.32	25	120	<5	3.49	<1	15	91	57	5.37	2.32	20	1.34	1050	2	0.63	18	1350	74	<5	<20	217	0.12	<10	85	10	9	57
S07-34350	0.2	7.14	20	395	<5	3.05	<1	11	60	54	3.84	2.44	20	1.54	940	<1	0.31	13	910	38	<5	<20	184	0.14	<10	96	<10	7	68
S07-34351	0.2	6.59	15	440	<5	3.72	<1	13	59	56	4.30	2.16	20	1.80	1337	5	0.38	17	1210	36	<5	<20	205	0.15	<10	174	<10	8	100
S07-34352	0.4	7.40	25	430	<5	3.76	<1	13	97	56	4.81	2.39	20	1.66	1251	3	0.73	20	1130	40	<5	<20	233	0.16	<10	153	<10	7	94
S07-34353	0.6	6.39	20	565	<5	2.54	1	12	224	81	3.82	2.30	20	1.17	815	6	1.19	21	840	40	<5	<20	214	0.15	<10	119	<10	7	153
S07-34354	0.2	7.59	25	670	<5	3.33	<1	15	134	63	4.24	2.19	20	1.66	1148	<1	2.02	28	1220	34	<5	<20	263	0.16	<10	131	<10	7	99
S07-34355	0.4	8.17	25	640	<5	4.13	<1	20	130	74	5.17	2.26	10	2.02	1425	<1	2.09	27	930	38	<5	<20	293	0.18	<10	191	<10	5	84
ATA:																													
<i>at:</i>																													
S07-34275	0.6	6.60	15	830	<5	1.07	<1	5	36	38	1.97	2.76	10	1.08	1760	<1	0.80	12	420	44	<5	<20	86	0.15	<10	31	<10	6	55
S07-34284	0.4	4.39	145	210	<5	2.16	<1	43	1016	26	5.03	1.91	<10	5.23	1974	6	0.37	327	560	34	10	<20	168	0.07	<10	128	<10	4	145
S07-34293	0.6	4.65	385	305	<5	4.93	<1	50	864	79	5.38	1.99	<10	3.64	2110	1	0.36	347	620	24	15	<20	251	0.06	<10	134	<10	4	184
S07-34319	1.2	4.83	15	100	<5	2.74	3	14	112	80	4.88	2.48	20	1.40	707	24	0.17	60	770	38	5	<20	150	0.06	<10	232	<10	6	159
S07-34328	1.0	6.39	15	240	<5	2.17	1	14	128	87	4.11	2.20	20	1.59	535	2	1.26	39	900	32	<5	<20	149	0.12	<10	140	<10	5	133
S07-34345	0.2	6.86	20	1115	<5	3.07	<1	8	67	67	2.61	2.07	20	1.52	700	5	0.85	19	660	34	<5	<20	153	0.15	<10	119	<10	9	84
<i>lit:</i>																													
S07-34275	0.8	6.49	10	795	<5	1.11	<1	4	40	41	1.88	2.60	10	0.94	1677	<1	0.75	12	370	40	<5	<20	75	0.14	<10	31	<10	5	60
S07-34311	0.4	4.55	35	155	<5	4.82	2	21	438	65	4.61	1.97	10	2.55	1107	20	0.16	103	900	24	5	<20	217	0.06	<10	193	<10	6	129
S07-34345	0.2	6.68	25	970	<5	3.00	<1	10	53	58	2.79	2.37	20	1.51	686	5	0.85	16	630	34	<5	<20	156	0.13	<10	116	<10	8	80
<i>lard:</i>																													
	0.5	5.56	30	1120	<5	2.56	<1	14	56	37	4.04	1.54	30	1.28	2473	4	1.23	30	1710	54	<5	<20	276	0.30	<10	108	<10	27	200
	0.4	5.42	30	1270	<5	2.30	<1	15	59	35	4.16	1.53	30	1.40	2569	5	1.16	34	1670	60	<5	<20	264	0.30	<10	105	<10	27	204
	0.4	5.67	35	1310	<5	2.51	<1	15	59	36	3.99	1.54	30	1.46	2642	5	1.20	35	1640	60	<5	<20	267	0.29	<10	107	<10	28	195

4 ACID DIGEST/ICP-FINISH
4 ACID DIGEST/AA-FINISH


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2285

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

10-Mar-08


Attention: Bob Singh

No. of samples received: 141
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-152
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-34356	0.10	0.003
2	S07-34357	0.04	0.001
3	S07-34358	0.05	0.001
4	S07-34359	0.37	0.011
5	S07-34360	0.94	0.027
6	S07-34361	<0.03	<0.001
7	S07-34362	0.13	0.004
8	S07-34363	0.54	0.016
9	S07-34364	0.22	0.007
10	S07-34365	<0.03	<0.001
11	S07-34366	<0.03	<0.001
12	S07-34367	* <0.03	<0.001
13	S07-34368	0.77	0.022
14	S07-34369	0.56	0.016
15	S07-34370	0.60	0.018
16	S07-34371	2.51	0.073
17	S07-34372	4.84	0.141
18	S07-34373	0.35	0.010
19	S07-34374	0.06	0.002
20	S07-34375	0.44	0.013
21	S07-34376	0.06	0.002
22	S07-34377	0.06	0.002
23	S07-34378	<0.03	<0.001
24	S07-34379	0.17	0.005
25	S07-34380	* 6.64	0.194
26	S07-34381	0.19	0.006
27	S07-34382	0.26	0.008
28	S07-34383	0.30	0.009

* = 30g FA



Jutta Jealouse
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	S07-34384	1.18	0.034
30	S07-34385	0.74	0.022
31	S07-34386	0.39	0.011
32	S07-34387	0.84	0.024
33	S07-34388	0.22	0.006
34	S07-34389	0.16	0.005
35	S07-34390	* 6.73	0.196
36	S07-34391	1.25	0.037
37	S07-34392	0.91	0.027
38	S07-34393	0.26	0.008
39	S07-34394	0.08	0.002
40	S07-34395	<0.03	<0.001
41	S07-34396	0.06	0.002
42	S07-34397	0.23	0.007
43	S07-34398	0.36	0.011
44	S07-34399	1.02	0.030
45	S07-34400	0.03	0.001
46	S07-34401	0.32	0.009
47	S07-34402	<0.03	<0.001
48	S07-34403	* <0.03	<0.001
49	S07-34404	0.18	0.005
50	S07-34405	<0.03	<0.001
51	S07-34406	0.03	0.001
52	S07-34407	0.60	0.017
53	S07-34408	0.60	0.017
54	S07-34409	0.06	0.002
55	S07-34410	0.34	0.010
56	S07-34411	0.28	0.008
57	S07-34412	0.42	0.012
58	S07-34413	0.41	0.012
59	S07-34414	0.40	0.012
60	S07-34415	0.22	0.006
61	S07-34416	1.82	0.053
62	S07-34417	0.08	0.002
63	S07-34418	<0.03	<0.001
64	S07-34419	1.56	0.045
65	S07-34420	0.67	0.019
66	S07-34421	<0.03	<0.001
67	S07-34422	0.69	0.020
68	S07-34423	0.22	0.006
69	S07-34424	0.10	0.003
70	S07-34425	<0.03	<0.001
71	S07-34426	<0.03	<0.001
72	S07-34427	0.51	0.015

* = 30g FA



 ECO TECH LABORATORY LTD.

Jutta Jealous

B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
73	S07-34428	<0.03	<0.001
74	S07-34429	0.05	0.001
75	S07-34430	0.03	<0.001
76	S07-34431	2.16	0.063
77	S07-34432	0.29	0.008
78	S07-34433	* 2.08	0.061
79	S07-34434	0.65	0.019
80	S07-34435	0.46	0.013
81	S07-34436	0.14	0.004
82	S07-34437	0.04	0.001
83	S07-34438	0.39	0.012
84	S07-34439	<0.03	<0.001
85	S07-34440	<0.03	<0.001
86	S07-34441	0.11	0.003
87	S07-34442	<0.03	<0.001
88	S07-34443	1.39	0.040
89	S07-34444	* <0.03	<0.001
90	S07-34445	0.86	0.025
91	S07-34446	1.93	0.056
92	S07-34447	0.55	0.016
93	S07-34448	0.11	0.003
94	S07-34449	0.66	0.019
95	S07-34450	0.03	0.001
96	S07-34451	0.03	0.001
97	S07-34452	0.03	0.001
98	S07-34453	0.07	0.002
99	S07-34454	0.04	0.001
100	S07-34455	0.04	0.001
101	S07-34456	0.21	0.006
102	S07-34457	0.12	0.004
103	S07-34458	0.11	0.003
104	S07-34459	<0.03	<0.001
105	S07-34460	0.06	0.002
106	S07-34461	<0.03	<0.001
107	S07-34462	<0.03	<0.001
108	S07-34463	<0.03	<0.001
109	S07-34464	<0.03	<0.001
110	S07-34465	<0.03	<0.001
111	S07-34466	<0.03	<0.001
112	S07-34467	<0.03	<0.001
113	S07-34468	<0.03	<0.001
114	S07-34469	<0.03	<0.001
115	S07-34470	<0.03	<0.001
116	S07-34471	* <0.03	<0.001

* = 30g FA



ECD TECH LABORATORY LTD.

 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
117	S07-34472	0.03	0.001
118	S07-34473	0.04	0.001
119	S07-34474	<0.03	<0.001
120	S07-34475	0.04	0.001
121	S07-34476	0.32	0.009
122	S07-34477	<0.03	<0.001
123	S07-34478	0.03	0.001
124	S07-34479	<0.03	<0.001
125	S07-34480	0.43	0.013
126	S07-34481	<0.03	<0.001
127	S07-34482	0.03	0.001
128	S07-34483	<0.03	<0.001
129	S07-34484	0.03	0.001
130	S07-34485	<0.03	<0.001
131	S07-34486	<0.03	<0.001
132	S07-34487	0.69	0.020
133	S07-34488	0.05	0.001
134	S07-34489	<0.03	<0.001
135	S07-34490	<0.03	<0.001
136	S07-34491	0.03	0.001
137	S07-34492	0.05	0.001
138	S07-34493	0.04	0.001
139	S07-34494	<0.03	<0.001
140	S07-34495	<0.03	<0.001
141	S07-34496	<0.03	<0.001

QC DATA:**Resplit:**

1	S07-34356	0.07	0.002
36	S07-34391	1.33	0.039
106	S07-34461	<0.03	<0.001
141	S07-34496	<0.03	<0.001

Standard:

OXI54	1.86	0.054
OXI54	1.90	0.055
OXI54	1.84	0.054
OXI54	1.84	0.054
OXI54	1.86	0.054
OXI54	1.83	0.053
OXI54	1.82	0.053
OXI54	1.89	0.055
OXI54	1.83	0.053

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

= 30g FA

JJ/nw

XLS/07



 ECO TECH LABORATORY LTD.

 Jutta Jealous
 B.C. Certified Assayer

ECH LABORATORY LTD.

Dallas Drive

OOPS, B.C.

T4

250-573-5700

250-573-4557

ICP CERTIFICATE OF ANALYSIS . . . 2007-2285

Skygold Ventures

615 - 800 W. Pender Street

Vancouver, BC

V6B 2V6

No. of samples received: 141

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-152

Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
S07-34356	0.4	7.11	15	315	<5	3.46	<1	16	133	42	4.35	1.54	10	1.62	1239	<1	2.95	24	760	32	<5	<20	285	0.20	<10	152	<10	7	42
S07-34357	0.4	7.61	10	540	<5	3.32	<1	22	127	105	4.97	2.83	10	2.10	1355	<1	1.87	31	660	32	<5	<20	257	0.19	<10	188	<10	6	77
S07-34358	0.6	7.61	10	515	<5	3.56	<1	21	96	99	4.62	2.81	10	1.99	1369	<1	1.92	31	660	32	<5	<20	266	0.19	<10	180	<10	6	62
S07-34359	0.4	7.00	10	580	<5	3.49	<1	11	125	65	3.50	2.67	20	1.45	1077	<1	1.42	18	720	28	<5	<20	233	0.17	<10	94	<10	11	55
S07-34360	0.2	7.27	15	505	<5	4.25	<1	19	152	53	4.72	2.92	10	2.07	1171	<1	1.11	30	810	30	<5	<20	266	0.18	<10	169	<10	7	62
S07-34361	0.6	7.12	15	730	<5	3.33	<1	16	146	102	4.09	2.49	20	1.52	868	<1	2.01	27	700	32	<5	<20	238	0.19	<10	177	<10	8	64
S07-34362	0.8	7.60	10	840	<5	4.02	<1	15	162	119	4.43	3.04	10	1.96	985	<1	0.57	23	930	34	<5	<20	233	0.22	<10	179	<10	7	68
S07-34363	0.6	7.92	20	800	<5	3.49	<1	19	204	146	4.76	3.08	20	1.72	897	<1	0.72	29	720	44	<5	<20	239	0.25	<10	170	<10	7	81
S07-34364	0.4	7.98	10	625	<5	3.72	<1	17	133	73	4.68	2.72	10	1.84	960	<1	2.29	26	1360	36	<5	<20	350	0.21	<10	173	<10	9	66
S07-34365	0.2	7.61	10	415	<5	3.25	<1	18	76	65	4.47	2.32	10	1.95	952	<1	2.69	22	850	30	<5	<20	291	0.18	<10	167	<10	6	72
S07-34366	0.2	8.30	5	520	<5	3.57	<1	18	69	62	5.08	2.64	10	2.08	1018	<1	2.70	23	910	28	<5	<20	293	0.19	<10	177	<10	6	72
S07-34367	<0.2	0.08	<5	10	<5	>10	<1	<1	1	<1	0.05	<0.01	<10	1.52	30	<1	0.02	26	40	4	<5	<20	5355	<0.01	<10	2	<10	<1	3
S07-34368	0.4	7.97	10	720	<5	3.49	2	18	92	74	4.76	3.44	10	1.94	1160	<1	0.98	21	800	94	<5	<20	280	0.22	<10	200	<10	6	195
S07-34369	2.8	8.04	20	780	<5	4.20	<1	26	187	64	6.01	3.37	10	1.89	1189	<1	0.77	32	920	50	<5	<20	336	0.20	<10	187	<10	6	80
S07-34370	0.4	8.24	10	730	<5	4.35	<1	16	137	73	4.37	3.38	20	1.62	1084	<1	1.13	19	990	34	<5	<20	280	0.22	<10	131	<10	8	95
S07-34371	0.2	7.35	20	605	<5	3.73	<1	17	95	60	4.68	2.82	10	1.61	1020	<1	1.35	21	840	34	<5	<20	276	0.24	<10	136	<10	10	50
S07-34372	1.0	8.25	30	755	<5	4.16	<1	21	73	52	5.46	3.67	10	1.83	1112	<1	0.81	26	990	38	<5	<20	292	0.25	<10	186	<10	7	53
S07-34373	0.4	8.09	20	665	<5	4.56	<1	18	74	47	4.86	3.53	<10	1.79	1203	<1	0.87	16	950	50	<5	<20	353	0.25	<10	166	<10	8	56
S07-34374	0.4	8.14	10	735	<5	5.17	<1	14	69	86	4.15	3.52	10	1.66	1174	<1	0.86	14	1050	28	<5	<20	284	0.22	<10	161	<10	9	43
S07-34375	0.8	7.80	15	715	<5	4.70	<1	15	116	70	4.39	3.33	20	1.52	951	<1	0.92	18	840	28	<5	<20	279	0.21	<10	139	<10	9	47
S07-34376	<0.2	6.66	<5	760	<5	3.48	<1	9	184	67	2.78	3.07	20	1.20	864	<1	0.42	10	730	32	<5	<20	286	0.16	<10	86	<10	10	37
S07-34377	0.2	7.75	10	645	<5	4.26	<1	16	56	77	4.33	2.88	10	1.68	1093	<1	1.75	19	1130	30	<5	<20	328	0.24	<10	168	<10	10	48
S07-34378	0.6	6.57	10	315	<5	4.14	<1	17	76	174	5.12	1.85	10	1.73	1140	<1	2.29	13	1490	26	<5	<20	306	0.28	<10	183	<10	12	50
S07-34379	0.6	6.80	5	495	<5	4.50	<1	24	107	184	6.20	2.99	20	1.85	1210	<1	0.54	12	2030	26	<5	<20	317	0.29	<10	211	<10	13	52
S07-34380	5.8	3.76	115	345	<5	0.36	<1	7	41	59	3.49	2.90	<10	0.27	218	5	0.47	20	410	24	60	<20	102	0.28	<10	50	<10	10	55

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
S07-34381	1.0	7.50	10	620	<5	4.68	<1	18	182	231	5.92	3.25	20	1.77	1213	<1	0.71	14	1830	34	<5	<20	380	0.31	<10	214	<10	13	56
S07-34382	0.8	7.61	5	505	<5	4.54	<1	20	60	209	6.10	2.88	20	1.66	1079	14	1.13	13	1700	30	<5	<20	324	0.27	<10	210	<10	14	61
S07-34383	0.8	7.87	10	565	<5	4.94	<1	18	101	209	5.86	3.42	20	1.62	1129	<1	0.65	12	1640	30	<5	<20	306	0.29	<10	205	<10	11	57
S07-34384	0.6	7.80	10	660	<5	4.85	<1	21	46	227	5.98	3.11	20	1.61	1126	1	0.93	12	1700	34	<5	<20	350	0.33	<10	205	<10	12	69
S07-34385	1.0	8.38	10	775	<5	4.92	<1	17	68	222	6.11	2.91	10	1.72	1149	<1	1.55	12	1650	38	<5	<20	374	0.30	<10	208	<10	13	66
S07-34386	0.8	7.34	10	785	<5	3.73	<1	20	85	234	6.30	2.70	20	1.77	1153	1	1.43	12	1860	32	<5	<20	263	0.28	<10	212	<10	12	96
S07-34387	0.8	6.46	<5	570	<5	3.31	<1	17	138	217	6.06	2.12	20	1.65	1014	<1	1.66	11	1790	26	<5	<20	282	0.31	<10	213	<10	13	65
S07-34388	0.6	6.93	10	515	<5	4.02	<1	21	132	247	6.55	1.99	20	1.81	1141	1	2.16	14	1940	30	<5	<20	413	0.38	<10	228	<10	14	56
S07-34389	0.6	6.86	5	445	<5	4.33	<1	20	46	204	6.49	1.80	20	1.83	1130	<1	2.82	12	1970	32	<5	<20	464	0.36	<10	225	<10	14	77
S07-34390	5.4	3.99	140	325	<5	0.40	<1	7	40	59	3.58	2.92	<10	0.28	229	5	0.48	21	420	24	65	<20	102	0.29	<10	51	<10	10	45
S07-34391	1.8	6.54	15	485	<5	4.32	<1	16	68	125	5.85	1.86	20	1.65	1185	<1	2.26	12	1790	162	<5	<20	460	0.35	<10	199	<10	13	51
S07-34392	0.6	6.90	20	470	<5	2.87	<1	15	109	55	5.26	2.26	20	1.56	997	<1	1.96	15	980	36	<5	<20	343	0.23	<10	143	<10	11	77
S07-34393	0.2	6.78	10	580	<5	3.44	<1	11	103	44	4.29	2.17	20	1.37	1095	<1	2.07	12	1140	30	<5	<20	353	0.23	<10	108	<10	10	60
S07-34394	0.2	7.39	5	590	<5	3.98	<1	11	54	42	4.13	2.38	10	1.51	1038	<1	2.30	12	1030	28	<5	<20	303	0.25	<10	128	<10	12	54
S07-34395	0.4	7.47	10	565	<5	3.55	<1	13	59	31	4.37	2.31	10	1.45	1077	<1	2.59	14	870	36	<5	<20	264	0.21	<10	125	<10	8	54
S07-34396	0.2	7.44	<5	875	<5	2.87	4	7	47	32	3.26	2.76	10	1.08	867	<1	1.57	8	620	32	<5	<20	212	0.17	<10	71	<10	7	353
S07-34397	1.4	7.20	5	995	<5	2.44	2	6	127	222	2.90	2.86	10	0.96	745	<1	1.32	9	560	256	<5	<20	226	0.14	<10	71	<10	5	227
S07-34398	0.2	7.04	5	595	<5	2.93	<1	12	80	38	3.83	2.57	10	1.31	1026	<1	1.56	14	800	28	<5	<20	222	0.25	<10	128	<10	8	78
S07-34399	0.2	7.56	5	490	<5	3.41	<1	12	56	76	4.48	2.42	10	1.62	1008	<1	2.43	11	1270	38	<5	<20	257	0.25	<10	127	<10	12	60
S07-34400	0.6	7.55	5	300	<5	3.89	<1	11	82	60	4.05	1.72	10	1.43	1092	<1	3.08	10	1780	30	<5	<20	321	0.26	<10	119	<10	14	44
S07-34401	0.6	8.31	10	565	<5	3.02	<1	14	38	54	4.87	2.38	10	1.68	983	<1	2.51	12	740	32	<5	<20	336	0.23	<10	143	<10	4	64
S07-34402	0.6	8.20	5	680	<5	3.15	<1	20	45	72	5.05	2.61	<10	1.84	1060	<1	2.55	17	740	30	<5	<20	312	0.24	<10	163	<10	5	60
S07-34403	<0.2	0.05	<5	10	<5	>10	<1	<1	<1	<1	0.04	<0.01	<10	1.91	27	<1	0.02	25	30	<2	<5	<20	5840	<0.01	<10	2	<10	<1	3
S07-34404	0.4	7.16	5	640	<5	3.41	<1	12	108	57	3.45	2.25	10	1.18	779	<1	2.24	10	720	24	<5	<20	318	0.18	<10	89	<10	7	46
S07-34405	0.4	6.96	<5	510	<5	2.74	<1	5	105	23	2.17	1.60	20	0.91	726	<1	3.34	5	580	34	<5	<20	416	0.14	<10	55	<10	8	25
S07-34406	0.4	6.85	<5	745	<5	2.56	<1	6	115	24	2.46	2.56	20	0.84	633	<1	1.25	7	520	30	<5	<20	279	0.15	<10	46	<10	10	45
S07-34407	0.4	7.80	10	650	<5	3.68	<1	16	115	59	4.54	2.53	10	1.70	1076	<1	1.73	16	790	46	<5	<20	289	0.26	<10	156	<10	9	69
S07-34408	0.6	8.19	5	615	<5	3.87	<1	13	80	53	4.41	2.36	10	1.66	1034	<1	2.31	14	800	32	<5	<20	323	0.22	<10	134	<10	6	58
S07-34409	0.2	8.39	10	655	<5	3.51	<1	16	75	41	4.99	2.64	10	1.89	1013	<1	1.51	18	850	34	<5	<20	297	0.26	<10	157	<10	8	81
S07-34410	0.4	6.59	<5	585	<5	2.55	<1	6	102	24	2.53	2.18	20	1.10	700	<1	1.25	8	700	28	<5	<20	249	0.15	<10	71	<10	7	46
S07-34411	0.6	8.40	10	725	<5	3.47	<1	18	133	105	5.11	2.96	10	2.10	1137	<1	0.94	18	870	40	<5	<20	379	0.30	<10	182	<10	8	52
S07-34412	0.4	8.23	10	495	<5	3.26	<1	12	87	30	4.55	2.23	10	1.84	979	<1	2.48	14	880	36	<5	<20	432	0.22	<10	136	<10	6	49
S07-34413	1.0	7.47	15	680	<5	3.58	<1	24	111	66	5.92	2.14	10	2.86	1193	<1	2.70	45	1220	54	<5	<20	388	0.27	<10	228	<10	9	116
S07-34414	1.0	7.58	15	505	<5	4.00	<1	25	148	72	6.07	2.22	10	2.94	1190	<1	2.74	49	1260	52	<5	<20	388	0.25	<10	240	<10	8	75
S07-34415	1.0	7.58	20	500	<5	4.05	<1	25	136	72	6.11	2.25	10	2.89	1189	<1	2.67	47	1250	56	<5	<20	385	0.26	<10	237	<10	9	73
S07-34416	1.6	7.24	25	550	<5	4.67	<1	22	111	147	5.50	2.08	20	2.41	1054	<1	2.91	41	1770	110	<5	<20	506	0.24	<10	207	<10	10	70
S07-34417	0.4	7.35	25	1180	<5	3.91	<1	29	162	60	6.13	2.69	10	3.62	1219	<1	1.99	70	1110	36	<5	<20	385	0.20	<10	246	<10	7	62
S07-34418	0.8	6.67	25	705	<5	4.09	<1	28	178	91	5.74	1.96	10	3.46	1176	<1	2.67	69	1170	38	<5	<20	442	0.16	<10	196	<10	7	59
S07-34419	0.8	6.26	30	460	<5	3.66	<1	32	286	101	6.04	2.29	10	4.00	1301	<1	1.99	101	1000	36	<5	<20	475	0.13	<10	272	<10	7	66
S07-34420	0.8	6.16	40	380	<5	4.38	<1	35	457	26	6.27	2.52	<10	4.76	1403	<1	1.13	139	1070	26	5	<20	476	0.11	<10	198	<10	7	55

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Li	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
S07-34421	0.4	6.16	40	780	<5	3.69	<1	34	436	49	6.06	2.68	10	4.95	1277	<1	0.86	136	950	22	5	<20	353	0.12	<10	194	<10	7	66
S07-34422	0.8	6.82	20	890	<5	4.70	<1	26	265	70	6.18	2.53	<10	4.37	1539	<1	1.61	88	1200	26	25	<20	415	0.14	<10	197	<10	7	64
S07-34423	2.4	7.71	15	1055	<5	4.18	<1	17	153	181	5.39	2.60	10	2.98	1183	<1	2.16	38	990	312	85	<20	373	0.17	<10	197	<10	7	77
S07-34424	1.2	6.34	20	1835	<5	1.90	<1	14	110	103	3.97	3.25	20	2.09	803	<1	0.18	40	770	36	20	<20	184	0.17	<10	160	<10	6	71
S07-34425	0.8	6.75	15	2170	<5	2.18	<1	11	63	28	3.48	3.48	20	2.01	816	<1	0.19	29	1660	30	5	<20	197	0.15	<10	106	<10	12	108
S07-34426	0.4	6.45	5	2085	<5	1.86	<1	9	56	31	3.56	3.35	20	2.05	801	<1	0.18	27	490	26	5	<20	170	0.15	<10	105	<10	6	63
S07-34427	1.0	5.21	15	1485	<5	2.01	<1	10	102	76	3.01	2.62	20	1.42	720	<1	0.12	52	740	26	10	<20	182	0.17	<10	93	<10	7	128
S07-34428	0.6	6.08	15	1970	<5	2.00	<1	12	118	73	3.26	3.16	30	1.91	828	<1	0.15	36	1520	28	<5	<20	231	0.16	<10	106	<10	10	110
S07-34429	0.8	7.46	10	2640	<5	0.94	<1	13	121	51	3.82	3.80	20	2.00	621	<1	0.20	34	450	32	<5	<20	115	0.22	<10	205	<10	6	83
S07-34430	0.4	6.70	10	2400	<5	1.14	<1	8	87	72	3.52	3.41	10	1.82	707	<1	0.18	28	390	28	<5	<20	126	0.20	<10	215	<10	6	50
S07-34431	1.4	5.54	20	735	<5	1.28	<1	18	110	147	4.61	2.81	10	1.44	670	3	0.14	54	410	30	<5	<20	134	0.17	<10	258	<10	6	47
S07-34432	0.8	5.96	15	2060	<5	1.34	<1	15	166	103	4.17	3.09	10	2.05	796	1	0.16	39	440	32	5	<20	154	0.18	<10	155	<10	5	65
S07-34433	5.2	4.41	100	305	<5	0.43	1	11	36	580	5.23	2.73	20	1.77	380	7	0.28	24	530	106	50	<20	73	0.29	<10	55	<10	11	682
S07-34434	1.2	4.54	10	815	<5	1.48	<1	13	277	85	3.71	2.28	10	1.61	701	3	0.10	44	410	24	<5	<20	152	0.13	<10	189	<10	5	50
S07-34435	0.8	5.87	15	910	<5	1.07	<1	16	143	97	3.83	3.00	20	1.44	559	3	0.15	48	560	40	<5	<20	115	0.19	<10	223	<10	6	120
S07-34436	0.6	7.59	10	2615	<5	1.64	<1	16	118	89	4.14	3.88	20	2.11	861	<1	0.23	42	600	34	<5	<20	170	0.24	<10	204	<10	7	100
S07-34437	0.8	6.45	15	2030	<5	1.26	<1	17	170	63	3.93	3.36	20	1.90	712	<1	0.19	46	500	30	<5	<20	139	0.19	<10	164	<10	5	114
S07-34438	0.6	6.33	15	970	<5	1.81	<1	13	134	105	4.11	3.18	10	1.85	897	3	0.17	39	420	34	<5	<20	200	0.16	<10	168	<10	5	108
S07-34439	0.6	7.00	20	2480	<5	1.53	<1	13	119	52	3.51	3.60	20	1.82	800	1	0.20	39	490	30	<5	<20	168	0.19	<10	153	<10	6	101
S07-34440	0.6	7.20	15	2585	<5	0.98	<1	12	128	30	3.61	3.70	20	1.96	657	<1	0.24	36	480	28	<5	<20	123	0.19	<10	119	<10	6	108
S07-34441	1.0	5.82	15	1315	<5	1.57	<1	15	174	97	4.24	2.91	20	1.92	838	<1	0.30	47	900	34	<5	<20	181	0.22	<10	121	<10	7	90
S07-34442	0.8	6.97	5	2340	<5	1.07	<1	12	117	71	3.57	3.60	20	1.81	571	1	0.23	35	480	30	<5	<20	137	0.18	<10	216	<10	4	117
S07-34443	1.0	5.78	35	975	<5	0.89	2	27	179	209	5.55	2.99	20	1.52	490	5	0.17	73	510	48	<5	<20	109	0.18	<10	313	<10	5	266
S07-34444	<0.2	0.04	<5	35	<5	>10	<1	<1	2	<1	0.04	<0.01	<10	1.67	20	<1	0.01	28	40	6	<5	<20	5661	<0.01	<10	1	<10	<1	1
S07-34445	1.2	5.90	30	945	<5	1.91	<1	32	223	277	4.62	2.98	10	1.57	859	6	0.16	73	560	40	<5	<20	189	0.15	<10	173	<10	5	85
S07-34446	0.8	5.82	25	740	<5	2.49	<1	20	197	81	4.22	2.96	20	1.66	971	<1	0.19	63	870	38	<5	<20	235	0.16	<10	150	<10	7	44
S07-34447	0.6	5.15	15	1545	<5	2.27	<1	15	158	96	3.15	2.62	20	1.50	1004	<1	0.13	46	550	30	<5	<20	209	0.19	<10	109	<10	6	39
S07-34448	0.4	5.68	15	1635	<5	2.24	<1	13	104	88	3.37	2.86	20	1.53	940	<1	0.16	56	490	28	<5	<20	211	0.22	<10	111	<10	6	76
S07-34449	0.6	5.25	25	435	<5	3.19	<1	13	229	117	3.59	2.66	20	1.34	1344	2	0.15	54	1100	32	<5	<20	265	0.16	<10	98	<10	7	119
S07-34450	0.4	4.66	25	1090	<5	2.22	<1	13	286	63	2.99	2.27	20	1.57	1620	<1	0.19	99	440	24	<5	<20	227	0.15	<10	84	<10	6	99
S07-34451	0.6	4.78	45	1115	<5	2.52	1	18	254	55	3.51	2.40	20	1.83	1894	<1	0.14	222	370	28	<5	<20	263	0.15	<10	96	<10	7	200
S07-34452	0.4	4.35	50	960	<5	2.60	1	16	261	62	3.00	1.90	20	1.66	1708	<1	0.08	174	460	24	<5	<20	264	0.17	<10	82	<10	8	147
S07-34453	0.2	4.67	20	990	<5	2.28	<1	11	280	43	2.32	2.16	20	1.26	1221	<1	0.22	71	430	22	<5	<20	230	0.18	<10	73	<10	8	103
S07-34454	0.2	4.60	20	1010	<5	2.32	<1	11	327	26	2.33	2.15	30	1.30	1234	2	0.15	70	450	22	<5	<20	237	0.17	<10	73	<10	8	78
S07-34455	0.4	4.12	20	920	<5	2.79	<1	14	257	34	2.82	1.91	20	1.34	1395	<1	0.18	98	380	24	<5	<20	283	0.17	<10	70	<10	7	64
S07-34456	0.6	3.56	25	555	<5	3.41	<1	14	372	48	2.99	1.66	20	1.42	1642	<1	0.07	108	370	24	<5	<20	327	0.13	<10	65	<10	7	30
S07-34457	0.4	4.61	35	1065	<5	3.69	<1	16	311	77	3.14	2.27	20	1.73	2262	<1	0.13	178	300	22	<5	<20	354	0.17	<10	88	<10	9	30
S07-34458	0.2	4.16	20	945	<5	4.40	<1	8	249	23	2.91	2.11	20	1.89	3217	<1	0.14	73	440	20	<5	<20	436	0.15	<10	74	<10	7	36
S07-34459	0.4	4.19	25	935	<5	2.82	<1	13	170	24	2.92	2.10	20	1.69	2334	<1	0.21	128	350	18	<5	<20	290	0.17	<10	79	<10	7	72
S07-34460	0.4	5.34	40	1090	<5	1.78	<1	18	224	86	3.27	2.61	20	1.74	1863	<1	0.21	173	400	22	<5	<20	194	0.20	<10	96	<10	7	137

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn	
S07-34461	0.2	5.82	40	1140	<5	1.72	<1	16	166	49	3.48	2.73	20	1.87	2089	<1	0.37	157	470	26	<5	<20	194	0.17	<10	95	<10	6	145
S07-34462	0.2	6.20	40	1190	<5	1.88	<1	16	166	41	3.62	2.72	30	1.90	2119	<1	0.35	157	470	26	<5	<20	196	0.19	<10	98	<10	6	116
S07-34463	0.8	6.00	35	1190	<5	2.01	1	14	166	148	3.56	2.72	30	1.87	2346	<1	0.45	189	490	28	<5	<20	215	0.17	<10	95	<10	6	170
S07-34464	0.6	5.87	40	1190	<5	1.55	<1	15	146	113	3.14	2.67	20	1.63	1818	<1	0.29	168	460	30	<5	<20	168	0.17	<10	92	<10	5	135
S07-34465	0.4	5.45	35	1115	<5	1.52	<1	13	150	62	3.27	2.58	20	1.73	1993	<1	0.30	110	380	30	<5	<20	168	0.16	<10	85	<10	5	71
S07-34466	0.8	4.33	30	830	<5	2.44	2	15	287	113	3.11	2.03	20	1.71	2472	<1	0.16	138	380	32	10	<20	240	0.13	<10	74	<10	5	232
S07-34467	0.6	4.13	20	795	<5	1.55	<1	14	186	47	2.58	1.94	10	1.52	1771	<1	0.23	76	320	24	<5	<20	175	0.13	<10	71	<10	5	60
S07-34468	0.4	4.10	30	770	<5	1.99	<1	13	163	70	2.89	1.94	20	1.69	2034	<1	0.25	98	380	32	<5	<20	210	0.13	<10	72	<10	5	137
S07-34469	1.6	4.79	30	890	<5	1.96	1	16	177	102	3.46	2.29	20	1.84	2215	<1	0.39	131	430	34	<5	<20	216	0.15	<10	77	<10	5	222
S07-34470	0.6	5.23	40	1020	<5	1.90	<1	19	147	142	3.24	2.41	20	1.72	2372	1	0.28	210	460	26	<5	<20	196	0.15	<10	94	<10	5	171
S07-34471	<0.2	0.05	<5	5	5	>10	<1	<1	2	<1	0.04	<0.01	<10	1.83	33	<1	0.01	27	40	2	<5	<20	5595	<0.01	<10	1	<10	<1	9
S07-34472	0.6	5.94	40	1215	<5	1.45	1	25	159	206	3.45	2.42	20	1.56	2023	3	0.40	241	350	38	<5	<20	154	0.17	<10	111	<10	5	211
S07-34473	0.6	5.22	35	945	<5	1.89	<1	18	206	77	3.41	2.19	20	1.63	2253	<1	0.36	148	400	36	<5	<20	195	0.16	<10	88	<10	5	118
S07-34474	0.8	4.66	30	815	<5	2.39	<1	14	162	31	3.17	2.10	20	1.81	2815	<1	0.36	115	540	36	<5	<20	248	0.14	<10	72	<10	5	106
S07-34475	1.4	5.64	40	1035	<5	2.42	<1	17	157	104	2.86	2.60	30	1.77	2800	1	0.50	173	540	44	<5	<20	255	0.17	<10	91	<10	5	156
S07-34476	0.2	4.70	35	370	<5	2.05	<1	24	167	56	3.88	2.15	20	1.62	2633	<1	0.33	147	410	36	<5	<20	204	0.14	<10	76	<10	4	95
S07-34477	0.6	6.51	35	1125	<5	1.96	<1	16	146	126	3.39	2.91	30	1.95	2792	<1	0.53	132	480	40	<5	<20	199	0.18	<10	99	<10	5	122
S07-34478	1.4	6.17	35	1025	<5	1.92	<1	18	143	182	3.74	2.81	30	2.13	2919	<1	0.55	204	570	42	<5	<20	206	0.17	<10	97	<10	5	156
S07-34479	1.0	5.23	35	915	<5	1.77	<1	16	172	75	2.86	2.44	30	1.76	2473	<1	0.37	153	460	38	<5	<20	194	0.15	<10	89	<10	5	123
S07-34480	0.8	5.70	115	315	<5	0.24	<1	7	24	30	3.30	4.18	10	0.34	160	3	0.09	15	490	20	40	<20	52	0.35	<10	66	<10	11	54
S07-34481	2.6	5.47	35	925	<5	1.82	<1	18	240	118	3.43	2.54	20	1.96	2638	<1	0.40	191	470	34	<5	<20	196	0.15	<10	92	<10	5	137
S07-34482	1.0	4.68	25	820	<5	3.93	<1	13	206	173	3.02	2.27	20	1.94	4362	<1	0.38	155	580	32	<5	<20	371	0.13	<10	78	<10	7	113
S07-34483	0.4	3.50	10	625	<5	1.87	<1	12	212	52	2.32	1.71	10	1.48	2250	<1	0.19	72	290	26	<5	<20	190	0.10	<10	62	<10	4	62
S07-34484	0.8	4.28	15	690	<5	2.09	<1	15	231	96	2.72	1.92	20	1.49	2116	<1	0.36	90	440	46	<5	<20	216	0.12	<10	74	<10	4	128
S07-34485	0.6	3.52	10	530	<5	2.42	<1	7	284	49	1.61	1.49	20	1.09	1418	<1	0.56	35	440	44	<5	<20	238	0.11	<10	42	<10	5	90
S07-34486	0.2	3.75	5	545	<5	2.43	<1	5	200	15	1.51	1.55	20	1.01	1226	<1	0.64	21	430	26	<5	<20	225	0.14	<10	37	<10	5	54
S07-34487	0.6	5.94	25	740	<5	3.50	<1	17	272	54	3.09	2.74	30	1.61	1667	1	0.57	109	490	42	5	<20	322	0.15	<10	83	<10	8	82
S07-34488	0.6	3.86	10	540	<5	1.83	<1	6	267	37	1.53	1.51	20	0.80	622	<1	0.73	27	410	20	<5	<20	171	0.13	<10	36	<10	5	39
S07-34489	0.2	3.62	10	505	<5	1.81	<1	4	175	25	1.44	1.42	20	0.75	481	<1	0.80	16	410	20	<5	<20	168	0.13	<10	32	<10	4	27
S07-34490	0.2	3.78	5	530	<5	2.24	<1	5	316	22	1.70	1.54	20	0.92	683	<1	0.66	19	450	20	5	<20	206	0.13	<10	37	<10	5	31
S07-34491	0.2	3.34	10	480	<5	1.77	<1	5	228	35	1.55	1.34	20	0.76	513	<1	0.78	17	390	20	5	<20	167	0.12	<10	32	<10	4	40
S07-34492	0.2	3.43	5	480	<5	1.86	<1	5	180	25	1.52	1.30	20	0.76	524	<1	0.75	16	390	18	<5	<20	172	0.13	<10	32	<10	4	43
S07-34493	<0.2	3.46	5	485	<5	1.85	<1	5	212	32	1.55	1.32	20	0.77	523	<1	0.80	17	380	18	<5	<20	180	0.12	<10	31	<10	4	32
S07-34494	<0.2	3.42	5	490	<5	1.79	<1	6	214	28	1.62	1.34	20	0.77	530	<1	0.82	18	390	20	<5	<20	177	0.12	<10	32	<10	4	37
S07-34495	0.2	3.43	5	475	<5	1.77	<1	5	214	32	1.53	1.29	20	0.76	518	<1	0.86	17	380	24	5	<20	179	0.12	<10	31	<10	4	41
S07-34496	<0.2	3.76	10	515	<5	1.85	<1	5	179	21	1.54	1.39	20	0.75	518	<1	0.80	16	410	24	<5	<20	175	0.15	<10	35	<10	6	35
S07-34356	0.4	7.02	15	315	<5	3.37	<1	17	129	40	4.39	1.55	10	1.61	1208	<1	2.88	22	750	30	<5	<20	280	0.19	<10	150	<10	6	50
S07-34365	<0.2	8.01	5	425	<5	3.43	<1	17	79	66	4.72	2.39	10	2.00	993	<1	2.81	22	880	26	<5	<20	298	0.19	<10	169	<10	7	75
S07-34374	0.2	8.07	10	715	<5	5.28	<1	15	67	82	4.10	3.41	10	1.62	1158	<1	0.85	15	1030	30	<5	<20	280	0.22	<10	157	<10	8	50
S07-34391	2.0	6.58	15	500	<5	4.36	<1	16	69	137	5.78	1.95	20	1.71	1195	<1	2.39	11	1800	160	<5	<20	474	0.36	<10	204	<10	13	50

IA:

if:

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn	
S07-34400	0.4	7.49	5	300	<5	3.73	<1	11	82	57	4.04	1.70	10	1.42	1082	<1	2.98	10	1760	30	<5	<20	320	0.26	<10	120	<10	13	48
S07-34409	0.4	8.11	10	640	<5	3.44	<1	16	72	39	4.69	2.59	10	1.84	987	<1	1.48	16	820	32	<5	<20	292	0.25	<10	154	<10	7	81
S07-34426	0.6	6.85	10	2155	<5	1.96	<1	11	58	34	3.73	3.47	20	2.12	844	<1	0.20	29	500	28	<5	<20	176	0.15	<10	110	<10	6	65
S07-34435	0.6	5.93	15	870	<5	1.05	<1	16	150	96	3.88	3.02	20	1.44	561	3	0.15	49	570	34	<5	<20	113	0.20	<10	223	<10	7	123
S07-34445	1.4	5.78	25	925	<5	1.81	<1	32	256	266	4.54	2.90	10	1.53	850	6	0.16	72	560	36	<5	<20	177	0.14	<10	169	<10	4	81
S07-34461	0.2	6.18	45	1165	<5	1.90	1	17	171	54	3.71	2.72	30	1.92	2121	<1	0.38	166	500	26	<5	<20	199	0.18	<10	95	<10	6	155
S07-34470	0.6	5.40	45	1085	<5	1.82	<1	20	155	154	3.38	2.62	30	1.84	2473	1	0.30	222	490	28	<5	<20	208	0.16	<10	100	<10	6	175
S07-34479	0.6	5.41	30	910	<5	1.89	<1	16	177	71	2.96	2.43	20	1.75	2512	<1	0.37	162	480	38	<5	<20	195	0.16	<10	89	<10	5	135


t:

S07-34356	0.4	7.13	10	305	<5	3.23	<1	16	140	44	4.49	1.57	10	1.63	1239	<1	3.08	22	770	32	<5	<20	288	0.18	<10	152	<10	7	48
S07-34391	1.8	6.74	20	505	<5	3.97	<1	17	61	130	5.82	1.98	20	1.72	1179	<1	2.41	12	1810	176	<5	<20	478	0.37	<10	210	<10	13	49
S07-34426	0.6	6.71	5	2120	<5	1.95	<1	9	58	29	3.55	3.40	20	2.05	847	<1	0.21	26	510	28	5	<20	183	0.16	<10	107	<10	7	61
S07-34461	0.4	6.13	45	1170	<5	1.69	<1	16	175	50	3.62	2.79	30	1.83	2010	1	0.39	167	490	22	<5	<20	186	0.19	<10	98	<10	7	134
S07-34496	<0.2	3.59	5	520	<5	1.72	<1	5	187	22	1.52	1.42	20	0.74	499	<1	0.82	16	390	24	<5	<20	172	0.15	<10	36	<10	6	37

ard:


0.4	5.65	20	1235	<5	2.46	<1	15	57	35	4.21	1.48	40	1.35	2509	4	1.31	33	1600	60	5	<20	248	0.34	<10	100	<10	28	214
0.4	5.45	20	1205	<5	2.36	<1	15	57	34	4.02	1.46	40	1.32	2423	4	1.30	32	1640	60	<5	<20	259	0.33	<10	108	<10	27	190
0.5	5.72	20	1270	<5	2.49	<1	15	60	36	4.09	1.47	40	1.41	2545	4	1.40	32	1630	60	<5	<20	262	0.34	<10	117	<10	29	195
0.5	5.77	25	1270	<5	2.40	<1	15	59	37	4.17	1.48	40	1.40	2562	5	1.15	33	1710	60	<5	<20	258	0.32	<10	113	<10	29	208
0.4	5.62	25	1235	<5	2.37	<1	15	59	36	4.20	1.44	30	1.34	2524	5	1.27	33	1700	62	<5	<20	260	0.33	<10	122	<10	28	280

ACID DIGEST/ICP-FINISH
ACID DIGEST/AA-FINISH



Jutta Jealous
B.C. Certified Assayer

ias/d2285bs



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2280R

Revised

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

5-Mar-08

Attention: Bob Singh

No. of samples received: 142
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-151
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-18879	<0.03	<0.001
2	S07-18880	<0.03	<0.001
3	S07-18881	<0.03	<0.001
4	S07-18882	<0.03	<0.001
5	S07-18883	<0.03	<0.001
6	S07-18884	<0.03	<0.001
7	S07-18885	<0.03	<0.001
8	S07-18886	<0.03	<0.001
9	S07-18887	0.05	0.002
10	S07-18888	<0.03	<0.001
11	S07-18890	<0.03	<0.001
12	S07-18891	<0.03	<0.001
13	S07-18892	* <0.03	<0.001
14	S07-18893	<0.03	<0.001
15	S07-18894	<0.03	<0.001
16	S07-18895	<0.03	<0.001
17	S07-18896	<0.03	<0.001
18	S07-18897	<0.03	<0.001
19	S07-18898	<0.03	<0.001
20	S07-18899	<0.03	<0.001
21	S07-18900	0.07	0.002
22	S07-18901	<0.03	<0.001
23	S07-18902	<0.03	<0.001
24	S07-18903	* 2.00	0.058
25	S07-18904	<0.03	<0.001
26	S07-18905	<0.03	<0.001
27	S07-18906	<0.03	<0.001
28	S07-18907	<0.03	<0.001
29	S07-18908	<0.03	<0.001
30	S07-18909	<0.03	<0.001

* = 30g FA

Jutta Jealouse
ECOTECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
31	S07-18910	<0.03	<0.001
32	S07-18911	<0.03	<0.001
33	S07-18912	<0.03	<0.001
34	S07-18913	<0.03	<0.001
35	S07-18914	<0.03	<0.001
36	S07-18915	<0.03	<0.001
37	S07-18916	<0.03	<0.001
38	S07-18917	<0.03	<0.001
39	S07-18918	<0.03	<0.001
40	S07-18919	<0.03	<0.001
41	S07-18920	<0.03	<0.001
42	S07-18921	<0.03	<0.001
43	S07-18922	0.13	0.004
44	S07-18923	<0.03	<0.001
45	S07-18924	<0.03	<0.001
46	S07-18925	<0.03	<0.001
47	S07-18926	<0.03	<0.001
48	S07-18927	<0.03	<0.001
49	S07-18928	<0.03	<0.001
50	S07-18929	<0.03	<0.001
51	S07-18930	<0.03	<0.001
52	S07-18931	0.03	0.001
53	S07-18932	<0.03	<0.001
54	S07-18933	<0.03	<0.001
55	S07-18934	<0.03	<0.001
56	S07-18935	<0.03	<0.001
57	S07-18936	<0.03	<0.001
58	S07-18937	<0.03	<0.001
59	S07-18938	<0.03	<0.001
60	S07-18939	<0.03	<0.001
61	S07-18940	<0.03	<0.001
62	S07-18941	6.49	0.189
63	S07-18942	0.24	0.007
64	S07-18943	<0.03	<0.001
65	S07-18944	<0.03	<0.001
66	S07-18945	<0.03	<0.001
67	S07-18946	<0.03	<0.001
68	S07-18947	<0.03	<0.001
69	S07-18948	<0.03	<0.001
70	S07-18949	<0.03	<0.001
71	S07-18950	0.33	0.010
72	S07-18951	0.75	0.022
73	S07-18952	0.32	0.009


* = 30g FA

John Bruce Jones
ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
74	S07-18953	0.20	0.006
75	S07-18954	0.14	0.004
76	S07-18955	0.23	0.007
77	S07-18956	0.29	0.008
78	S07-18957	0.76	0.022
79	S07-18958	0.87	0.025
80	S07-18959	0.44	0.013
81	S07-18960	* <0.03	<0.001
82	S07-18961	1.30	0.038
83	S07-18962	0.87	0.025
84	S07-18963	0.99	0.029
85	S07-18964	0.25	0.007
86	S07-18965	0.30	0.009
87	S07-18966	0.65	0.019
88	S07-18967	0.79	0.023
89	S07-18968	0.16	0.005
90	S07-18969	0.86	0.025
91	S07-18970	0.53	0.015
92	S07-18971	0.48	0.014
93	S07-18972	1.21	0.035
94	S07-18973	0.47	0.014
95	S07-18974	0.14	0.004
96	S07-18975	<0.03	<0.001
97	S07-18976	0.04	0.001
98	S07-18977	0.19	0.006
99	S07-18978	<0.03	<0.001
100	S07-18979	9.94	0.290
101	S07-18980	* 6.61	0.193
102	S07-18981	0.12	0.003
103	S07-18982	0.03	0.001
104	S07-18983	<0.03	<0.001
105	S07-18984	<0.03	<0.001
106	S07-18985	<0.03	<0.001
107	S07-18986	0.05	0.001
108	S07-18987	<0.03	<0.001
109	S07-18988	<0.03	<0.001
110	S07-18989	<0.03	<0.001
111	S07-18990	<0.03	<0.001
112	S07-18991	<0.03	<0.001
113	S07-18992	<0.03	<0.001
114	S07-18993	<0.03	<0.001
115	S07-18994	<0.03	<0.001
116	S07-18995	* <0.03	<0.001

* = 30g FA


ECOTECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
117	S07-18996	<0.03	<0.001
118	S07-18997	<0.03	<0.001
119	S07-18998	<0.03	<0.001
120	S07-18999	<0.03	<0.001
121	S07-19000	<0.03	<0.001
122	S07-19001	<0.03	<0.001
123	S07-19002	<0.03	<0.001
124	S07-19003	<0.03	<0.001
125	S07-19004	<0.03	<0.001
126	S07-19005	<0.03	<0.001
127	S07-19006	* 2.07	0.060
128	S07-19007	<0.03	<0.001
129	S07-19008	<0.03	<0.001
130	S07-19009	<0.03	<0.001
131	S07-19010	<0.03	<0.001
132	S07-19011	0.17	0.005
133	S07-19012	<0.03	<0.001
134	S07-19013	<0.03	<0.001
135	S07-19014	<0.03	<0.001
136	S07-19015	<0.03	<0.001
137	S07-19016	<0.03	<0.001
138	S07-19017	<0.03	<0.001
139	S07-19018	<0.03	<0.001
140	S07-19019	<0.03	<0.001
141	S07-19020	<0.03	<0.001
142	S07-19021	<0.03	<0.001


QC DATA:**Resplit:**

1	S07-18879	<0.03	<0.001
36	S07-18915	<0.03	<0.001
71	S07-18950	0.49	0.014
106	S07-18985	<0.03	<0.001
141	S07-19020	<0.03	<0.001

Standard:

OXI54	1.84	0.054
OXI54	1.88	0.055
OXI54	1.88	0.055
OXI54	1.87	0.055
OXI54	1.90	0.055
OXI54	1.84	0.054
OXI54	1.88	0.055

* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

kygold Ventures AK7-2280


5-Mar-08

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
OXI54		1.84	0.054
OXI54		1.88	0.055
OXI54		1.82	0.053
OXI54		1.85	0.054
OXI54		1.88	0.055

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA
JJ/nw
XLS/07


ECOTECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

TECH LABS LABORATORY LTD.
41 Dallas Drive
MLOOPS, B.C.
V6T4

ICP CERTIFICATE OF ANALYSIS X 2007-2280R
Revised

Skygold Ventures
615 - 800 W. Pender Street
Vancouver, BC
V6B 2V6

Phone: 250-573-5700
Fax: 250-573-4557

No. of samples received: 142
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-151
Samples submitted by: Tasha Gainer

Concentrations in ppm unless otherwise reported

Lot #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-18879	0.2	1.64	55	105	<5	5.06	<1	18	410	5	3.38	0.52	<10	3.85	1789	<1	0.08	165	200	10	5	<20	658	0.02	<10	46	<10	5	40
2	S07-18880	0.6	4.69	110	455	<5	4.19	<1	26	644	34	4.30	1.93	<10	4.56	1620	<1	0.56	224	500	18	10	<20	235	0.04	<10	80	<10	5	55
3	S07-18881	0.8	5.52	25	1110	<5	1.89	<1	11	160	120	2.41	2.15	10	1.58	995	<1	0.68	39	640	24	15	<20	166	0.11	<10	43	<10	7	29
4	S07-18882	0.6	5.40	30	1075	<5	1.98	<1	9	158	136	2.59	2.22	10	1.73	1078	<1	0.72	45	580	26	15	<20	156	0.10	<10	42	<10	5	40
5	S07-18883	0.6	6.17	35	1090	<5	1.59	<1	13	130	75	3.48	2.20	10	2.26	1839	<1	0.90	48	660	32	<5	<20	136	0.12	<10	81	<10	7	51
6	S07-18884	<0.2	5.05	55	770	<5	0.71	<1	13	113	64	2.62	1.33	10	1.03	1968	<1	0.84	49	460	36	5	<20	66	0.09	<10	66	<10	4	57
7	S07-18885	0.6	5.95	45	1070	<5	1.12	<1	15	90	28	3.22	1.91	10	1.69	2119	<1	0.51	59	770	36	<5	<20	86	0.11	<10	77	<10	6	72
8	S07-18886	0.6	3.89	60	715	<5	2.11	<1	19	187	23	2.90	1.42	10	1.61	2166	<1	0.42	75	380	36	5	<20	159	0.09	<10	69	<10	4	51
9	S07-18887	0.4	4.86	40	1180	<5	3.98	<1	29	696	4	4.67	2.56	<10	6.07	3454	<1	0.40	170	650	22	10	<20	392	0.07	<10	156	<10	5	82
10	S07-18888	0.4	5.02	55	765	<5	4.00	<1	33	568	48	4.51	1.87	<10	5.34	2849	<1	0.36	209	610	24	10	<20	311	0.09	<10	124	<10	6	75
11	S07-18890	0.6	3.66	10	1225	<5	1.92	<1	23	167	81	3.35	1.38	10	1.50	2878	<1	0.23	78	410	32	<5	<20	149	0.11	<10	91	<10	5	75
12	S07-18891	0.4	5.56	15	1510	<5	1.26	<1	27	102	43	4.45	1.99	20	1.91	2909	<1	0.60	74	550	40	<5	<20	110	0.14	<10	94	<10	7	127
13	S07-18892	0.2	7.58	<5	540	<5	3.03	<1	11	79	35	4.38	1.14	10	1.37	834	3	2.99	29	840	30	<5	<20	319	0.38	<10	108	<10	18	50
14	S07-18893	0.6	5.12	20	740	<5	2.48	<1	31	277	31	4.58	1.35	10	3.39	2568	<1	0.75	164	630	26	5	<20	199	0.11	<10	131	<10	5	72
15	S07-18894	0.2	5.32	15	745	<5	1.01	<1	23	86	86	3.78	1.26	20	1.98	1540	<1	1.11	57	500	40	<5	<20	128	0.17	<10	94	<10	6	54
16	S07-18895	0.4	5.52	20	1000	<5	1.30	<1	24	93	36	3.90	2.01	20	2.28	2112	<1	0.61	64	490	38	<5	<20	112	0.17	<10	127	<10	5	69
17	S07-18896	0.6	5.00	35	1010	<5	1.47	<1	30	255	48	4.01	2.11	20	2.39	2376	<1	0.40	100	450	38	<5	<20	133	0.15	<10	126	<10	5	87
18	S07-18897	0.6	5.95	40	1275	<5	2.28	<1	39	348	111	4.55	2.72	10	4.04	3202	<1	0.35	172	590	28	<5	<20	196	0.16	<10	213	<10	7	121
19	S07-18898	0.4	6.70	45	1360	<5	2.57	<1	49	508	86	5.01	2.84	10	4.44	3471	<1	0.40	257	670	34	10	<20	223	0.15	<10	226	<10	7	142
20	S07-18899	0.4	5.79	45	1205	<5	3.17	<1	38	373	10	5.29	2.44	20	4.43	4214	<1	0.31	212	800	30	5	<20	262	0.14	<10	216	<10	7	134
21	S07-18900	1.0	3.93	35	545	<5	1.84	<1	30	220	91	4.09	1.53	20	1.85	2442	<1	0.21	92	510	56	<5	<20	157	0.10	<10	81	<10	5	53
22	S07-18901	0.4	5.38	15	1130	<5	1.24	<1	13	148	49	2.88	1.80	20	1.78	2077	<1	0.40	42	640	30	<5	<20	102	0.13	<10	58	<10	8	56
23	S07-18902	0.4	6.13	15	1360	<5	0.87	<1	12	120	42	2.67	2.17	20	1.75	1644	<1	0.39	34	420	28	<5	<20	79	0.13	<10	60	<10	8	54
24	S07-18903	4.8	4.51	120	170	<5	0.52	1	12	36	573	5.28	2.68	10	1.83	403	7	0.23	24	540	106	50	<20	74	0.29	<10	53	<10	11	647
25	S07-18904	1.0	4.16	15	585	<5	1.21	<1	21	220	145	3.42	1.35	20	1.75	2147	<1	0.63	69	470	30	5	<20	108	0.11	<10	60	<10	5	76

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y
26	S07-18905	0.4	4.80	20	880	<5	1.57	<1	20	288	75	3.68	1.71	10	2.46	2863	<1	0.67	108	420	32	5	<20	142	0.10	<10	55	<10	6
27	S07-18906	1.0	6.20	10	1170	<5	1.66	<1	20	144	273	3.57	1.97	10	1.74	2927	<1	0.76	45	500	62	<5	<20	134	0.13	<10	125	<10	5
28	S07-18907	0.6	5.41	15	755	<5	1.02	<1	26	243	57	4.42	1.63	20	1.60	2784	<1	1.21	64	520	38	<5	<20	96	0.15	<10	85	<10	6
29	S07-18908	0.8	5.45	10	935	<5	1.33	<1	22	231	189	3.78	1.90	20	1.98	2966	<1	0.86	55	540	30	<5	<20	127	0.14	<10	128	<10	6
30	S07-18909	0.2	5.36	<5	1265	<5	0.90	<1	5	124	14	1.78	2.32	20	1.50	1982	<1	0.97	14	290	24	<5	<20	107	0.13	<10	74	<10	6
31	S07-18910	0.4	6.05	10	1025	<5	0.76	<1	14	168	88	3.03	2.23	20	1.50	2133	<1	0.99	35	390	28	<5	<20	85	0.14	<10	39	<10	6
32	S07-18911	0.4	5.32	5	1060	<5	0.92	<1	11	212	25	2.41	2.29	20	1.52	1830	<1	0.25	27	350	22	<5	<20	84	0.13	<10	38	<10	8
33	S07-18912	0.4	5.88	5	1210	<5	1.11	<1	7	118	15	2.19	2.63	20	1.43	2084	3	0.32	23	520	24	<5	<20	107	0.16	<10	69	<10	7
34	S07-18913	0.4	6.05	<5	1150	<5	0.67	<1	4	112	12	1.96	2.45	10	1.36	1421	<1	0.29	10	410	26	<5	<20	60	0.13	<10	26	<10	7
35	S07-18914	0.4	5.47	<5	1080	<5	0.56	<1	4	159	35	2.01	2.40	10	1.33	869	<1	0.29	11	270	24	<5	<20	57	0.13	<10	19	<10	5
36	S07-18915	0.2	4.49	30	1015	<5	1.34	<1	13	350	25	2.30	2.37	10	3.23	1103	<1	0.25	97	240	22	5	<20	196	0.10	<10	37	<10	8
37	S07-18916	<0.2	0.07	<5	15	<5	>10	<1	<1	2	1	0.52	0.03	<10	>10	193	<1	0.03	2	200	<2	<5	<20	53	<0.01	<10	3	<10	<1
38	S07-18917	0.2	6.36	40	1065	<5	1.54	<1	10	167	15	2.15	2.41	10	1.99	1665	<1	0.29	65	380	32	<5	<20	121	0.14	<10	45	<10	10
39	S07-18918	0.2	5.32	<5	940	<5	0.57	<1	5	122	16	1.95	2.24	10	1.54	1284	<1	0.21	12	310	22	<5	<20	59	0.13	<10	34	<10	8
40	S07-18919	0.2	5.97	5	1005	<5	1.19	<1	6	115	33	1.91	2.43	20	1.59	1906	<1	0.29	19	630	34	<5	<20	106	0.15	<10	55	<10	7
41	S07-18920	0.4	6.72	5	1130	<5	2.43	<1	8	121	18	2.31	2.69	20	2.48	2478	<1	0.31	21	850	32	<5	<20	363	0.14	<10	77	<10	9
42	S07-18921	1.4	4.70	<5	785	<5	0.61	1	4	143	12	1.66	2.25	10	1.47	854	<1	0.15	11	250	514	<5	<20	60	0.11	<10	26	<10	5
43	S07-18922	0.8	6.00	10	925	<5	1.02	6	10	191	54	2.77	2.85	10	2.08	1526	<1	0.22	46	300	260	<5	<20	76	0.14	<10	32	<10	10
44	S07-18923	0.4	5.19	20	750	<5	2.03	<1	14	239	42	2.54	2.34	10	2.94	1601	<1	0.30	75	380	26	<5	<20	143	0.11	<10	63	<10	8
45	S07-18924	0.2	4.91	40	520	<5	3.66	<1	26	442	18	3.46	2.07	10	4.24	2536	<1	0.39	238	410	24	5	<20	187	0.10	<10	62	<10	6
46	S07-18925	0.2	5.36	20	510	<5	3.88	<1	25	363	11	3.86	2.07	10	4.50	2736	<1	0.67	167	480	26	5	<20	196	0.10	<10	99	<10	6
47	S07-18926	0.4	5.14	15	595	<5	1.57	<1	15	205	42	2.69	2.09	10	2.65	1519	<1	0.50	85	340	24	<5	<20	92	0.11	<10	37	<10	9
48	S07-18927	0.2	6.03	5	555	<5	1.92	<1	9	271	24	2.68	2.11	10	1.74	928	<1	1.05	26	430	30	<5	<20	125	0.14	<10	44	<10	6
49	S07-18928	0.8	6.20	15	330	<5	5.82	<1	30	342	74	5.52	2.05	<10	4.83	1839	<1	1.53	107	890	26	5	<20	365	0.10	<10	176	<10	5
50	S07-18929	0.2	5.76	10	335	<5	1.09	<1	10	229	47	2.33	1.51	10	2.19	1073	<1	1.66	65	480	26	<5	<20	117	0.13	<10	52	<10	7
51	S07-18930	<0.2	5.48	10	345	<5	1.01	<1	11	194	40	2.27	1.51	10	2.14	1080	<1	1.71	61	490	22	<5	<20	112	0.14	<10	51	<10	5
52	S07-18931	<0.2	5.80	25	330	<5	2.34	<1	25	331	20	3.86	1.37	10	4.56	1995	<1	0.82	214	580	22	<5	<20	133	0.16	<10	77	<10	8
53	S07-18932	<0.2	4.93	5	255	<5	1.22	<1	9	180	29	2.44	0.96	<10	2.69	840	<1	1.42	94	360	20	<5	<20	112	0.12	<10	39	<10	4
54	S07-18933	<0.2	4.40	20	55	<5	5.71	<1	47	584	48	4.90	0.71	<10	7.54	1900	<1	0.60	339	590	18	5	<20	247	0.06	<10	119	<10	6
55	S07-18934	0.2	4.88	30	150	<5	5.92	<1	44	517	48	5.63	1.71	<10	6.70	1586	<1	0.53	279	840	28	10	<20	277	0.07	<10	162	<10	5
56	S07-18935	0.4	4.89	35	245	<5	5.70	<1	33	453	74	4.62	1.97	<10	5.15	1635	<1	0.36	184	710	26	5	<20	338	0.07	<10	129	<10	5
57	S07-18936	0.6	5.31	15	255	<5	1.47	<1	10	158	48	2.21	1.20	20	1.81	793	<1	1.98	41	350	24	<5	<20	129	0.12	<10	49	<10	5
58	S07-18937	0.4	5.08	10	485	<5	1.02	<1	8	117	46	1.99	1.76	20	1.53	825	<1	1.73	17	370	22	<5	<20	119	0.14	<10	57	<10	6
59	S07-18938	0.4	4.71	45	340	<5	4.43	<1	29	483	18	3.48	1.97	10	4.96	1697	14	0.37	220	410	36	10	<20	239	0.08	<10	109	<10	6
60	S07-18939	0.2	3.80	55	95	<5	6.29	<1	49	908	43	4.77	1.30	<10	8.82	1736	<1	0.37	475	480	18	10	<20	254	0.02	<10	105	<10	4
61	S07-18940	0.4	4.17	70	145	<5	4.60	<1	40	745	11	4.53	1.84	<10	7.80	1644	<1	0.38	386	530	18	15	<20	245	0.04	<10	96	<10	5
62	S07-18941	6.0	4.17	170	135	<5	0.37	<1	8	39	49	3.55	3.01	<10	0.28	239	6	0.53	23	430	26	65	<20	90	0.29	<10	51	<10	9
63	S07-18942	0.2	4.52	50	145	<5	4.14	<1	36	548	57	4.41	1.90	<10	7.08	1148	<1	0.42	273	560	16	10	<20	172	0.07	<10	97	<10	6
64	S07-18943	<0.2	4.54	15	135	<5	2.63	<1	28	389	31	4.55	1.81	<10	5.73	1017	<1	0.33	171	650	20	10	<20	121	0.11	<10	123	<10	4
65	S07-18944	0.2	4.35	55	265	<5	2.97	<1	41	653	22	4.86	1.69	<10	5.97	1542	<1	0.29	248	620	24	10	<20	209	0.08	<10	134	<10	4

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y
66	S07-18945	0.2	4.74	25	130	<5	2.22	<1	18	174	37	3.35	1.79	20	1.72	1057	<1	0.23	51	410	30	<5	<20	129	0.09	<10	54	<10	6
67	S07-18946	0.6	4.40	45	150	<5	4.24	<1	45	734	57	5.18	1.68	<10	7.40	1875	<1	0.37	323	670	20	15	<20	218	0.06	<10	141	<10	4
68	S07-18947	0.4	4.63	55	175	<5	4.45	<1	49	807	79	5.42	1.83	<10	6.28	2008	<1	0.35	349	670	20	10	<20	227	0.08	<10	164	<10	4
69	S07-18948	0.2	4.63	65	170	<5	3.47	<1	48	588	68	5.55	1.77	<10	6.25	1751	<1	0.36	274	770	20	5	<20	186	0.11	<10	147	<10	5
70	S07-18949	0.6	4.50	65	165	<5	4.11	<1	43	538	65	5.15	1.60	<10	6.08	1936	<1	0.29	249	710	20	10	<20	197	0.07	<10	127	<10	4
71	S07-18950	0.6	4.54	25	225	<5	4.36	<1	24	255	79	4.81	1.79	10	4.72	1602	9	0.19	97	820	28	<5	<20	230	0.09	<10	166	<10	7
72	S07-18951	1.0	4.24	15	65	<5	3.46	2	17	123	63	4.34	1.72	20	1.49	925	24	0.06	76	940	26	<5	<20	169	0.07	<10	209	<10	6
73	S07-18952	1.4	5.24	30	65	<5	3.27	3	18	144	116	4.76	2.16	20	1.42	884	30	0.10	80	990	36	5	<20	161	0.09	<10	253	<10	6
74	S07-18953	1.8	5.20	20	60	<5	3.36	3	17	139	74	4.65	2.12	20	1.50	909	27	0.09	76	1070	62	10	<20	170	0.11	<10	256	<10	7
75	S07-18954	1.6	4.68	15	95	<5	3.26	2	15	111	58	4.39	1.66	20	1.49	933	25	0.08	66	900	44	5	<20	162	0.10	<10	237	<10	6
76	S07-18955	1.6	4.75	20	70	<5	3.69	3	15	136	67	4.63	1.74	20	1.59	1053	28	0.08	71	920	80	5	<20	169	0.08	<10	223	<10	6
77	S07-18956	1.2	5.24	15	95	<5	3.02	2	16	127	64	4.29	2.24	20	1.36	878	25	0.24	56	770	68	<5	<20	164	0.10	<10	213	<10	6
78	S07-18957	1.6	7.72	15	75	<5	4.59	4	22	68	87	5.07	2.31	20	1.62	1296	10	1.62	37	1290	246	5	<20	271	0.16	<10	178	50	7
79	S07-18958	1.2	5.88	15	85	<5	3.47	4	18	96	100	4.67	2.21	10	1.54	1007	10	0.60	45	850	214	<5	<20	221	0.13	<10	192	<10	6
80	S07-18959	1.0	4.87	15	130	<5	2.69	2	15	136	119	4.48	2.09	20	1.28	899	35	0.16	75	820	38	<5	<20	152	0.10	<10	233	<10	6
81	S07-18960	<0.2	0.06	<5	10	<5	>10	<1	<1	2	<1	0.05	0.01	<10	1.74	20	<1	0.01	21	40	4	<5	<20	5632	<0.01	<10	3	<10	<1
82	S07-18961	1.4	7.09	10	115	<5	3.24	1	18	64	74	4.02	2.35	10	1.40	750	10	1.74	31	740	34	<5	<20	219	0.17	<10	217	<10	5
83	S07-18962	0.8	6.70	15	55	<5	3.12	<1	15	117	83	4.38	2.22	20	1.34	739	13	1.73	33	780	28	<5	<20	218	0.15	<10	218	<10	6
84	S07-18963	1.0	7.34	10	125	<5	2.77	<1	10	212	85	3.42	2.27	20	1.42	841	8	1.16	29	790	30	<5	<20	260	0.15	<10	151	<10	8
85	S07-18964	0.6	6.27	10	180	<5	2.30	<1	8	164	79	2.63	1.85	20	1.10	467	11	1.87	24	560	30	<5	<20	194	0.14	<10	115	<10	8
86	S07-18965	0.8	7.75	15	190	<5	4.47	<1	11	114	70	3.91	2.41	20	1.79	930	3	1.52	19	780	42	<5	<20	256	0.17	<10	88	<10	10
87	S07-18966	1.0	6.22	15	200	<5	3.47	<1	11	185	58	3.16	1.81	20	1.40	831	5	1.78	28	620	50	<5	<20	233	0.15	<10	104	<10	6
88	S07-18967	0.8	6.84	15	110	<5	4.49	<1	17	150	89	4.64	2.02	10	1.69	985	12	1.84	26	870	36	<5	<20	245	0.14	<10	168	<10	6
89	S07-18968	0.8	6.90	15	240	<5	3.10	<1	11	144	61	2.87	2.25	20	1.32	615	3	1.79	18	580	36	<5	<20	174	0.18	<10	115	<10	7
90	S07-18969	0.8	8.41	20	205	<5	3.83	<1	10	212	58	3.37	3.03	30	1.74	839	7	1.05	13	1200	34	<5	<20	193	0.18	<10	98	<10	12
91	S07-18970	0.6	6.42	15	180	<5	2.20	<1	9	202	40	2.93	2.29	20	0.95	500	6	1.24	14	600	30	<5	<20	140	0.15	<10	79	<10	8
92	S07-18971	0.6	7.39	15	105	<5	3.47	<1	11	109	70	3.70	2.97	10	1.44	744	1	1.22	13	640	36	<5	<20	160	0.17	<10	104	<10	8
93	S07-18972	0.6	6.15	20	135	<5	3.17	<1	12	206	61	3.68	2.12	20	1.18	753	7	1.18	17	860	32	<5	<20	142	0.15	<10	135	<10	7
94	S07-18973	0.4	7.12	10	185	<5	2.86	<1	9	178	78	3.37	2.33	20	1.15	799	7	1.61	16	780	30	<5	<20	154	0.19	<10	100	<10	6
95	S07-18974	0.6	7.06	15	90	<5	3.27	<1	14	98	66	4.69	2.63	10	1.35	940	48	0.96	14	920	34	<5	<20	144	0.20	<10	111	<10	6
96	S07-18975	0.4	7.10	10	490	<5	3.96	<1	12	164	39	4.36	2.50	20	1.63	1129	<1	1.16	14	960	30	<5	<20	187	0.21	<10	96	<10	6
97	S07-18976	0.4	7.28	5	225	<5	3.92	<1	12	37	74	4.54	2.73	20	1.49	1077	8	0.83	13	820	32	<5	<20	168	0.17	<10	98	<10	6
98	S07-18977	0.6	7.60	<5	395	<5	3.32	<1	14	54	51	4.66	2.72	30	1.83	1004	<1	0.64	12	1140	38	<5	<20	162	0.17	<10	119	<10	7
99	S07-18978	0.2	6.40	5	955	<5	2.73	<1	15	72	41	4.47	2.40	20	1.65	1020	<1	0.91	20	1760	30	<5	<20	156	0.17	<10	111	<10	7
100	S07-18979	1.6	6.97	5	1120	<5	3.89	4	9	35	84	4.40	2.43	20	1.92	1511	<1	0.52	9	1200	760	<5	<20	284	0.18	<10	85	<10	7
101	S07-18980	5.8	3.96	190	135	<5	0.39	<1	7	39	52	3.44	2.93	<10	0.27	241	6	0.55	22	410	24	70	<20	89	0.29	<10	52	<10	9
102	S07-18981	0.2	6.91	<5	1025	<5	3.25	<1	11	33	38	4.26	2.76	20	1.76	1313	<1	0.47	9	1240	36	<5	<20	179	0.18	<10	96	<10	6
103	S07-18982	<0.2	7.97	5	975	<5	4.45	<1	15	62	47	5.23	3.05	20	2.01	1568	<1	0.67	13	1560	32	<5	<20	250	0.21	<10	122	<10	7
104	S07-18983	0.4	7.27	5	900	<5	3.49	<1	13	74	37	4.82	2.89	20	1.96	1138	<1	0.53	12	1480	26	<5	<20	205	0.22	<10	100	<10	7
105	S07-18984	0.6	7.71	<5	975	<5	3.36	<1	18	63	44	4.82	3.08	10	2.35	1171	<1	0.85	17	1460	28	<5	<20	212	0.18	<10	198	<10	7

#.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Li%	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn	
06	S07-18985	0.4	9.06	15	965	<5	3.58	<1	21	82	60	5.78	3.75	10	2.31	1345	<1	0.75	21	1190	36	<5	<20	199	0.19	<10	197	<10	5	88
07	S07-18986	0.8	7.20	15	795	<5	4.21	5	14	115	59	4.84	2.77	10	1.92	1435	<1	1.21	15	1060	48	<5	<20	267	0.17	<10	140	<10	7	470
08	S07-18987	0.4	6.76	10	975	<5	3.02	<1	14	62	60	3.71	2.71	20	1.33	964	5	1.12	22	890	30	<5	<20	209	0.13	<10	121	<10	7	58
09	S07-18988	0.6	7.77	15	875	<5	3.61	<1	17	64	94	4.68	2.66	10	1.86	1325	<1	2.13	21	860	38	<5	<20	280	0.15	<10	209	<10	5	91
10	S07-18989	0.6	8.08	15	715	<5	3.97	<1	22	67	138	4.81	2.32	10	1.94	1505	<1	2.31	23	780	36	<5	<20	356	0.16	<10	205	<10	5	99
11	S07-18990	0.4	7.90	10	550	<5	2.77	<1	19	80	91	4.70	2.05	10	1.59	1139	<1	2.30	22	640	34	<5	<20	322	0.17	<10	179	<10	5	67
12	S07-18991	0.4	8.27	10	800	<5	2.57	<1	13	35	42	4.43	2.33	20	1.86	1095	<1	1.47	15	960	32	<5	<20	357	0.22	<10	88	<10	8	87
13	S07-18992	0.2	7.84	15	700	<5	3.34	<1	20	53	58	4.78	1.90	10	1.88	1100	<1	2.03	19	860	34	<5	<20	401	0.18	<10	152	<10	5	76
14	S07-18993	0.2	8.10	15	710	<5	5.32	<1	17	49	60	5.32	1.92	10	2.08	1545	<1	1.90	20	990	36	<5	<20	421	0.20	<10	178	<10	5	75
15	S07-18994	0.4	8.43	10	745	<5	4.01	<1	13	58	136	4.88	1.86	10	1.88	1136	2	2.41	31	850	32	<5	<20	351	0.22	<10	230	<10	5	64
16	S07-18995	<0.2	0.13	<5	15	<5	>10	<1	<1	1	<1	0.10	0.04	<10	1.70	21	<1	0.02	28	40	<2	<5	<20	5747	<0.01	<10	3	<10	<1	9
17	S07-18996	0.2	8.15	15	790	<5	3.88	<1	17	61	107	5.44	1.99	<10	2.19	1369	<1	1.87	25	900	32	<5	<20	356	0.21	<10	208	<10	4	72
18	S07-18997	0.4	8.32	15	490	<5	3.76	<1	25	80	114	5.40	1.24	10	1.97	1645	<1	2.70	63	790	34	<5	<20	363	0.24	<10	200	<10	5	70
19	S07-18998	0.4	7.63	10	520	<5	2.23	<1	21	79	131	4.46	1.28	10	1.71	1198	<1	2.52	53	700	30	<5	<20	326	0.19	<10	165	<10	5	105
20	S07-18999	0.2	7.15	10	470	<5	2.89	<1	21	69	124	4.45	1.11	10	1.85	1351	<1	2.41	62	850	28	<5	<20	313	0.19	<10	169	<10	6	73
21	S07-19000	0.2	8.15	15	515	<5	2.14	<1	19	66	74	4.92	1.26	10	2.01	1321	<1	2.52	51	640	30	<5	<20	328	0.22	<10	205	<10	4	74
22	S07-19001	0.2	7.17	15	345	<5	4.89	<1	17	64	70	4.10	0.88	10	1.65	1885	<1	2.93	23	630	30	<5	<20	309	0.20	<10	136	<10	7	45
23	S07-19002	0.2	8.12	15	520	<5	2.50	<1	20	69	109	4.79	1.24	10	1.86	1287	<1	2.64	31	570	34	<5	<20	298	0.20	<10	166	<10	4	82
24	S07-19003	0.2	7.49	15	460	<5	2.93	<1	17	59	109	4.56	1.08	10	1.95	1274	<1	2.10	28	580	32	<5	<20	336	0.19	<10	169	<10	4	84
25	S07-19004	0.2	7.77	10	690	<5	3.34	<1	9	70	47	3.71	1.55	10	1.46	979	<1	1.96	14	600	30	<5	<20	393	0.15	<10	92	<10	6	55
26	S07-19005	0.6	8.44	15	450	<5	4.66	<1	12	66	47	4.46	1.07	10	1.58	1224	<1	3.18	15	980	32	<5	<20	573	0.19	<10	127	<10	6	49
27	S07-19006	5.0	4.49	195	230	<5	0.50	1	12	37	567	5.08	2.37	10	1.91	413	7	0.25	25	540	110	50	<20	81	0.28	<10	55	<10	11	650
28	S07-19007	0.6	8.55	15	725	<5	5.00	<1	18	44	39	4.44	1.66	10	1.56	1231	<1	2.80	16	1100	34	<5	<20	515	0.20	<10	134	<10	6	74
29	S07-19008	0.4	7.38	10	540	<5	5.49	<1	12	54	41	4.22	1.23	10	1.70	1174	<1	3.13	15	890	28	<5	<20	567	0.19	<10	125	<10	6	80
30	S07-19009	0.4	8.24	15	475	<5	5.71	<1	19	62	52	4.94	1.15	10	2.24	1332	<1	3.50	23	860	36	<5	<20	865	0.21	<10	181	<10	7	61
31	S07-19010	0.4	8.13	15	305	<5	6.61	<1	18	58	35	4.81	0.81	<10	2.03	1439	<1	4.39	22	910	32	<5	<20	930	0.20	<10	164	<10	5	36
32	S07-19011	0.2	7.89	15	340	<5	6.38	<1	18	64	64	4.76	0.78	<10	1.91	1415	<1	4.28	18	1070	36	<5	<20	766	0.20	<10	177	<10	6	46
33	S07-19012	0.2	8.56	15	675	<5	4.86	<1	18	52	44	4.71	1.49	<10	2.01	1163	<1	3.30	18	870	34	<5	<20	636	0.21	<10	176	<10	5	60
34	S07-19013	0.4	8.33	20	680	<5	4.77	<1	20	65	104	5.30	1.80	10	1.78	1041	<1	2.99	24	890	36	<5	<20	540	0.19	<10	171	<10	6	63
35	S07-19014	0.2	8.45	15	990	<5	4.10	<1	19	56	76	5.25	2.05	<10	1.81	1051	<1	1.96	22	890	32	<5	<20	423	0.23	<10	177	<10	5	75
36	S07-19015	0.4	8.89	25	1125	<5	3.25	<1	20	72	71	5.21	2.33	10	1.80	1002	<1	1.64	23	960	34	<5	<20	347	0.23	<10	173	<10	5	79
37	S07-19016	0.4	8.66	15	985	<5	3.16	<1	13	42	59	4.88	2.12	10	1.94	1200	<1	1.91	17	1060	34	<5	<20	320	0.26	<10	139	<10	6	78
38	S07-19017	0.4	8.28	15	845	<5	3.98	<1	10	32	68	4.21	1.70	20	1.49	978	<1	2.14	11	1040	34	<5	<20	407	0.26	<10	121	<10	7	67
39	S07-19018	0.2	7.88	15	715	<5	3.58	<1	12	41	41	3.89	1.25	20	1.40	888	<1	2.57	12	1030	26	<5	<20	408	0.24	<10	103	<10	11	58
40	S07-19019	0.2	8.74	20	790	<5	4.13	<1	13	43	45	4.59	1.31	20	1.50	985	<1	2.91	14	1070	34	<5	<20	443	0.24	<10	110	<10	11	65
41	S07-19020	0.2	8.41	<5	690	<5	4.40	<1	12	32	61	4.01	1.30	10	1.40	1018	<1	2.78	14	960	30	<5	<20	432	0.27	<10	104	<10	14	61
42	S07-19021	<0.2	8.20	<5	595	<5	4.83	<1	12	34	41	4.19	1.07	20	1.43	1073	<1	2.80	12	1040	30	<5	<20	446	0.28	<10	118	<10	16	60

DATA:


reat:


1	S07-18879	0.2	1.73	60	100	<5	5.18	<1	19	427	5	3.50	0.52	<10	3.91	1817	<1	0.08	172	210	12	5	<20	667	0.02	<10	46	<10	5	44
10	S07-18888	0.5	5.27	55	745	<5	4.23	<1	32	546	49	4.67	1.90	10	5.24	2917	<1	0.38	209	620	28	15	<20	299	0.09	<10	122	<10	6	77
19	S07-18898	0.5	7.01	50	1465	<5	2.71	<1	55	516	90	5.14	2.91	10	4.85	3500	<1	0.42	279	710	38	10	<20	231	0.17	<10	239	<10	7	150

#.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn	
6	S07-18915	0.2	4.57	30	960	<5	1.42	<1	14	349	24	2.43	2.36	10	3.08	1122	<1	0.27	105	270	24	5	<20	185	0.11	<10	37	<10	8	52
5	S07-18924	0.2	4.51	35	510	<5	3.37	<1	25	457	17	3.22	2.00	10	4.15	2378	<1	0.38	224	390	22	5	<20	187	0.09	<10	62	<10	6	58
4	S07-18933	<0.2	4.46	20	55	<5	5.96	<1	47	536	46	4.95	0.72	<10	7.37	1877	<1	0.64	335	590	18	5	<20	238	0.06	<10	120	<10	6	68
1	S07-18950	0.4	4.42	25	205	<5	4.33	<1	23	265	81	4.69	1.71	10	4.55	1522	9	0.19	94	780	26	<5	<20	224	0.09	<10	166	<10	7	109
0	S07-18959	1.4	4.96	15	115	<5	2.74	2	15	135	117	4.60	2.11	20	1.26	912	35	0.16	75	830	36	5	<20	157	0.10	<10	233	<10	6	209
9	S07-18968	0.8	6.87	15	250	<5	2.83	<1	11	154	62	3.00	2.39	20	1.36	608	3	1.91	18	580	32	<5	<20	179	0.18	<10	121	<10	8	64
06	S07-18985	0.4	8.59	15	1000	<5	3.64	<1	19	89	63	5.56	3.67	10	2.39	1228	<1	0.80	20	1080	36	<5	<20	208	0.17	<10	201	<10	6	83
15	S07-18994	0.2	8.26	10	730	<5	3.93	<1	12	56	132	4.81	1.83	10	1.86	1125	2	2.33	30	840	34	<5	<20	348	0.22	<10	224	<10	5	66
24	S07-19003	0.2	7.78	15	470	<5	3.15	<1	17	61	114	4.72	1.11	10	1.99	1313	<1	2.14	29	600	34	<5	<20	344	0.19	<10	174	<10	5	83
plit:																														
1	S07-18879	0.3	1.53	55	100	<5	5.21	<1	17	448	6	3.48	0.47	<10	4.00	1806	<1	0.08	161	190	10	5	<20	682	0.02	<10	41	<10	5	42
6	S07-18915	0.2	4.75	40	1010	<5	1.46	<1	15	296	20	2.41	2.14	10	3.00	1167	<1	0.23	99	250	22	<5	<20	177	0.12	<10	37	<10	5	44
1	S07-18950	0.6	4.45	20	200	<5	4.33	<1	22	273	83	4.59	1.85	10	4.66	1572	16	0.17	90	760	28	<5	<20	218	0.09	<10	172	<10	7	115
06	S07-18985	0.4	8.52	15	900	<5	3.60	<1	19	83	58	5.27	3.39	10	2.17	1260	<1	0.68	20	1160	34	<5	<20	191	0.18	<10	180	<10	5	83
11	S07-19020	0.2	8.45	<5	685	<5	4.65	<1	10	36	59	3.95	1.32	20	1.40	1007	<1	2.86	14	970	30	<5	<20	432	0.28	<10	105	<10	14	60
andard:																														
1-3		0.5	5.82	20	1265	<5	2.42	<1	15	58	35	4.11	1.44	30	1.40	2583	5	1.29	33	1710	52	<5	<20	237	0.33	<10	104	<10	28	193
1-3		0.6	5.93	20	1275	<5	2.39	<1	15	59	34	4.19	1.41	30	1.39	2612	5	1.21	33	1750	54	<5	<20	245	0.33	<10	112	<10	27	208
1-3		0.6	5.57	20	1275	<5	2.20	<1	14	59	38	4.02	1.52	40	1.29	2577	4	1.17	29	1700	49	<5	<20	239	0.28	<10	118	<10	29	204
1-3		0.6	5.42	30	1215	<5	2.42	<1	14	56	34	4.08	1.53	30	1.36	2536	5	1.21	31	1790	58	<5	<20	227	0.29	<10	100	<10	27	202
1-3		0.4	5.89	20	1225	<5	2.38	<1	15	57	35	4.03	1.54	40	1.39	2522	5	1.21	31	1650	58	<5	<20	230	0.30	<10	108	<10	28	197

4 ACID DIGEST/ICP-FINISH
4 ACID DIGEST/AA-FINISH

W
280s
/07


ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2282

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

4-Mar-08


Attention: Bob Singh

No. of samples received: 119
Sample Type: Core
Project: **Spanish Mountain**
Shipment #: **SMC-07-153**
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-19027	<0.03	<0.001
2	S07-19028	<0.03	<0.001
3	S07-19029	<0.03	<0.001
4	S07-19030	<0.03	<0.001
5	S07-19031	<0.03	<0.001
6	S07-19032	<0.03	<0.001
7	S07-19033	<0.03	<0.001
8	S07-19034	<0.03	<0.001
9	S07-19035	<0.03	<0.001
10	S07-19036	<0.03	<0.001
11	S07-19037	<0.03	<0.001
12	S07-19038	0.12	0.003
13	S07-19039	1.01	0.030
14	S07-19040	0.46	0.013
15	S07-19041	0.67	0.020
16	S07-19042	0.16	0.005
17	S07-19043	0.87	0.025
18	S07-19044	1.16	0.034
19	S07-19045	0.42	0.012
20	S07-19046	0.48	0.014
21	S07-19047	0.09	0.003
22	S07-19048	<0.03	<0.001
23	S07-19049	<0.03	<0.001
24	S07-19050	<0.03	<0.001
25	S07-19051	0.04	0.001
26	S07-19052	<0.03	<0.001
27	S07-19053	<0.03	<0.001
28	S07-19054	0.61	0.018

* = 30g FA



Jutta Jealouze
B.C. Certified Assayer

ECO TECH LABORATORY LTD.

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	S07-19055	<0.03	<0.001
30	S07-19056	0.91	0.026
31	S07-19057	0.23	0.007
32	S07-19058	0.01	0.000
33	S07-19059	1.11	0.032
34	S07-19060	0.14	0.004
35	S07-19061	0.07	0.002
36	S07-19062	0.06	0.002
37	S07-19063	0.59	0.017
38	S07-19064	0.12	0.004
39	S07-19065	* <0.03	<0.001
40	S07-19066	0.11	0.003
41	S07-19067	0.29	0.008
42	S07-19068	0.11	0.003
43	S07-19069	0.08	0.002
44	S07-19070	<0.03	<0.001
45	S07-19071	0.05	0.001
46	S07-19072	0.04	0.001
47	S07-19073	0.06	0.002
48	S07-19074	0.06	0.002
49	S07-19075	* 6.62	0.193
50	S07-19076	0.04	0.001
51	S07-19077	0.12	0.004
52	S07-19078	<0.03	<0.001
53	S07-19079	0.28	0.008
54	S07-19080	<0.03	<0.001
55	S07-19081	<0.03	<0.001
56	S07-19082	0.12	0.004
57	S07-19083	3.95	0.115
58	S07-19084	<0.03	<0.001
59	S07-19085	0.15	0.004
60	S07-19086	0.05	0.001
61	S07-19087	0.03	0.001
62	S07-19088	0.16	0.005
63	S07-19089	<0.03	<0.001
64	S07-19090	<0.03	<0.001
65	S07-19091	<0.03	<0.001
66	S07-19092	0.17	0.005
67	S07-19093	0.16	0.005
68	S07-19094	0.07	0.002
69	S07-19095	0.08	0.002
70	S07-19096	0.08	0.002
71	S07-19097	0.07	0.002

* = 30g FA




ECOTECH LABORATORY LTD.

 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
72	S07-19098	0.05	0.001
73	S07-19099	<0.03	<0.001
74	S07-19100	0.03	0.001
75	S07-19101	* <0.03	<0.001
76	S07-19102	<0.03	<0.001
77	S07-19103	<0.03	<0.001
78	S07-19104	<0.03	<0.001
79	S07-19105	0.04	0.001
80	S07-19106	<0.03	<0.001
81	S07-19107	<0.03	<0.001
82	S07-19108	<0.03	<0.001
83	S07-19109	<0.03	<0.001
84	S07-19110	<0.03	<0.001
85	S07-19111	* 2.04	0.059
86	S07-19112	0.08	0.002
87	S07-19113	0.05	0.001
88	S07-19114	<0.03	<0.001
89	S07-19115	<0.03	<0.001
90	S07-19116	<0.03	<0.001
91	S07-19117	0.18	0.005
92	S07-19118	0.32	0.009
93	S07-19119	0.12	0.003
94	S07-19120	0.04	0.001
95	S07-19121	0.08	0.002
96	S07-19122	0.20	0.006
97	S07-19123	0.05	0.002
98	S07-19124	0.03	0.001
99	S07-19125	0.04	0.001
100	S07-19126	0.03	0.001
101	S07-19127	0.03	0.001
102	S07-19128	0.07	0.002
103	S07-19129	0.34	0.010
104	S07-19130	0.11	0.003
105	S07-19131	* 0.43	0.013
106	S07-19132	0.15	0.004
107	S07-19133	0.05	0.001
108	S07-19134	0.05	0.002
109	S07-19135	0.04	0.001
110	S07-19136	0.11	0.003
111	S07-19137	0.09	0.003
112	S07-19138	0.06	0.002
113	S07-19139	0.04	0.001
114	S07-19140	0.18	0.005

* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
115	S07-19141	<0.03	<0.001
116	S07-19142	<0.03	<0.001
117	S07-19143	0.43	0.012
118	S07-19144	0.03	0.001
119	S07-19145	0.66	0.019

QC DATA:

Resplit:

1	S07-19027	<0.03	<0.001
36	S07-19062	0.09	0.003
71	S07-19097	0.18	0.005
106	S07-19132	0.11	0.003


Standard:

OXI54	1.88	0.055
OXI54	1.86	0.054
OXI54	1.86	0.054
OXI54	1.80	0.052
OXI54	1.88	0.055
OXI54	1.86	0.054
OXI54	1.82	0.053
OXI54	1.84	0.054
OXI54	1.90	0.055
OXI54	1.86	0.054
OXI54	1.84	0.054

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw
XLS/07



ECOTECH LABORATORY LTD.

Jutta Jealous
B.C. Certified Assayer

CO TEC. LAB. ATORY LTD.
 1041 Dallas Drive
 AMLOOPS, B.C.
 BC 6T4

ICP CERTIFICATE OF ANALYSIS AK 2007-2282

Skygold Ventures
 615 - 800 W. Pender Street
 Vancouver, BC
 V6B 2V6

Phone: 250-573-5700
 Fax: 250-573-4557

No. of samples received: 119
 Sample Type: Core
 Project: Spanish Mountain
 Shipment #: SMC-07-153
 Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-19027	0.2	8.99	5	230	<5	3.74	<1	19	40	79	5.49	0.42	10	2.30	1070	<1	3.97	24	1010	34	<5	<20	457	0.42	<10	219	<10	18	71
2	S07-19028	<0.2	8.08	5	320	<5	3.22	<1	19	38	91	5.29	0.59	10	2.36	1058	<1	3.42	22	850	30	<5	<20	350	0.35	<10	226	<10	13	74
3	S07-19029	<0.2	8.64	<5	305	<5	3.62	<1	19	41	88	5.66	0.59	<10	2.46	1132	<1	3.26	23	900	32	<5	<20	374	0.36	<10	239	<10	14	76
4	S07-19030	<0.2	0.18	<5	10	<5	>10	<1	<1	2	<1	0.13	<0.01	<10	1.76	32	<1	0.02	24	50	<2	<5	<20	6096	<0.01	<10	4	<10	<1	4
5	S07-19031	0.2	9.17	<5	535	<5	4.37	<1	20	34	52	5.64	1.04	<10	2.44	1221	<1	2.95	24	950	36	<5	<20	416	0.27	<10	238	<10	12	76
6	S07-19032	<0.2	8.79	<5	455	<5	4.23	<1	20	31	71	5.11	0.89	<10	2.05	1156	<1	3.41	20	890	34	<5	<20	380	0.27	<10	204	<10	9	68
7	S07-19033	<0.2	8.22	5	270	<5	3.84	<1	20	38	70	4.52	0.52	10	1.77	1033	<1	3.39	23	860	32	<5	<20	646	0.41	<10	219	<10	17	60
8	S07-19034	<0.2	8.54	<5	380	<5	4.46	<1	20	68	82	5.14	0.80	<10	2.10	1269	<1	3.30	21	820	34	<5	<20	498	0.34	<10	203	<10	13	71
9	S07-19035	<0.2	8.09	<5	350	<5	6.24	<1	14	73	59	4.54	0.87	10	1.60	1245	<1	2.66	17	860	34	<5	<20	501	0.33	<10	174	<10	18	62
10	S07-19036	<0.2	7.61	<5	555	<5	4.19	<1	8	77	45	3.01	1.71	20	1.04	701	<1	1.86	9	710	30	<5	<20	520	0.16	<10	82	<10	10	48
11	S07-19037	<0.2	6.92	<5	630	<5	4.29	<1	7	119	53	2.86	2.16	20	0.96	688	<1	1.44	10	740	28	<5	<20	360	0.16	<10	75	<10	7	39
12	S07-19038	<0.2	7.55	5	635	<5	5.64	<1	16	153	80	4.87	2.97	10	1.87	1251	<1	1.36	24	1100	32	<5	<20	294	0.19	<10	184	<10	6	88
13	S07-19039	<0.2	7.48	5	505	<5	4.83	<1	17	111	187	6.34	2.90	20	1.83	1256	<1	1.28	14	1730	32	<5	<20	292	0.28	<10	214	<10	10	67
14	S07-19040	<0.2	8.58	10	750	<5	5.42	<1	17	127	229	6.77	3.01	20	2.06	1476	<1	1.26	14	1980	40	<5	<20	495	0.29	<10	232	<10	12	81
15	S07-19041	<0.2	7.46	15	575	<5	4.81	<1	25	106	289	7.30	2.89	20	1.79	1333	<1	1.30	16	2030	36	<5	<20	406	0.24	<10	227	<10	11	77
16	S07-19042	0.6	7.28	5	450	<5	5.08	<1	18	98	226	5.94	1.01	20	1.58	1251	1	1.19	13	1860	34	<5	<20	314	0.33	<10	204	<10	12	76
17	S07-19043	0.8	7.85	15	825	<5	5.05	<1	11	106	137	5.14	1.06	20	1.63	1219	<1	1.56	11	1710	44	<5	<20	450	0.30	<10	212	<10	12	65
18	S07-19044	0.8	7.17	25	600	<5	4.30	<1	16	205	239	5.42	1.06	10	1.62	1154	<1	2.52	14	1850	38	<5	<20	553	0.28	<10	180	<10	12	60
19	S07-19045	0.8	5.53	105	375	<5	0.21	<1	8	24	29	3.52	4.32	10	0.33	156	3	0.11	15	480	22	40	<20	52	0.34	<10	66	<10	12	54
20	S07-19046	0.2	5.24	15	420	<5	2.94	<1	11	235	24	3.68	1.24	10	0.87	738	<1	1.30	14	880	24	<5	<20	309	0.18	<10	80	<10	9	58
21	S07-19047	<0.2	6.45	10	525	<5	3.36	<1	11	202	41	3.53	1.13	10	1.02	911	<1	1.50	17	800	30	<5	<20	267	0.18	<10	123	<10	6	67
22	S07-19048	<0.2	5.79	<5	695	<5	3.00	<1	3	98	8	2.06	1.38	10	0.62	824	<1	1.25	7	430	22	<5	<20	266	0.13	<10	39	<10	4	49
23	S07-19049	0.4	6.23	<5	620	<5	2.90	<1	6	92	17	2.58	1.33	10	0.85	878	<1	1.98	8	460	22	<5	<20	263	0.15	<10	63	<10	4	48
24	S07-19050	<0.2	7.51	<5	580	<5	3.89	<1	13	96	67	4.30	1.01	10	1.43	1244	<1	2.39	14	1170	32	<5	<20	294	0.20	<10	121	<10	8	71
25	S07-19051	0.2	7.23	5	740	<5	3.70	<1	10	154	83	4.05	1.01	10	1.39	1098	<1	1.14	13	910	34	<5	<20	273	0.18	<10	108	<10	6	60

Et #.	Sample	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
26	S07-19052	0.8	6.92	<5	645	<5	3.63	<1	9	175	44	3.59	1.18	20	1.17	882	<1	1.60	12	560	28	<5	<20	266	0.18	<10	101	<10	7	70
27	S07-19053	0.4	6.97	<5	605	<5	3.61	<1	10	124	54	3.62	1.01	10	1.19	903	<1	1.74	12	590	26	<5	<20	277	0.17	<10	103	<10	5	64
28	S07-19054	0.4	7.78	10	775	<5	3.38	<1	17	152	77	4.53	1.15	10	1.73	1224	<1	1.51	20	710	138	<5	<20	259	0.24	<10	161	<10	6	108
29	S07-19055	0.4	8.23	10	745	<5	3.23	<1	18	145	64	4.88	1.15	<10	1.88	1090	<1	1.95	19	820	30	<5	<20	286	0.24	<10	174	<10	7	77
30	S07-19056	<0.2	8.05	10	725	<5	3.19	<1	18	90	61	4.68	1.26	<10	1.82	1113	<1	1.71	17	860	32	<5	<20	306	0.22	<10	187	<10	3	59
31	S07-19057	0.4	8.45	15	755	<5	3.55	<1	24	135	78	5.29	1.02	<10	1.94	1200	<1	2.22	22	890	76	<5	<20	381	0.23	<10	174	<10	4	114
32	S07-19058	0.2	8.22	<5	585	<5	3.53	<1	17	79	61	4.95	1.02	<10	1.89	1127	<1	3.83	17	880	32	<5	<20	563	0.23	<10	183	<10	4	64
33	S07-19059	0.6	7.90	5	460	<5	4.32	<1	14	95	73	4.31	1.12	10	1.70	1215	<1	4.44	16	820	34	<5	<20	774	0.21	<10	156	<10	5	43
34	S07-19060	0.4	6.90	5	445	<5	3.47	<1	13	126	58	3.54	1.02	10	1.18	862	<1	3.23	14	680	28	<5	<20	547	0.19	<10	116	<10	8	49
35	S07-19061	0.2	6.43	<5	540	<5	2.47	<1	6	145	50	2.22	1.38	20	0.80	644	<1	2.98	9	590	26	<5	<20	362	0.14	<10	57	<10	7	41
36	S07-19062	0.4	6.72	<5	595	<5	2.46	<1	12	195	64	3.48	1.14	20	1.20	848	<1	2.05	14	820	26	<5	<20	300	0.17	<10	108	<10	6	70
37	S07-19063	0.4	8.23	15	680	<5	3.36	<1	16	159	42	4.82	1.20	10	1.62	1054	<1	2.05	21	1220	36	<5	<20	443	0.22	<10	170	<10	7	42
38	S07-19064	0.6	7.92	10	400	<5	3.02	<1	17	107	121	4.62	1.04	10	1.69	985	<1	3.89	17	940	32	<5	<20	429	0.23	<10	153	<10	5	70
39	S07-19065	<0.2	0.08	<5	15	<5	>10	<1	<1	2	<1	0.50	0.03	<10	>10	182	<1	0.02	2	180	<2	<5	<20	51	<0.01	<10	3	<10	<1	10
40	S07-19066	0.6	7.48	5	400	<5	2.77	<1	18	79	89	4.83	1.30	<10	1.62	1091	<1	4.45	17	740	38	<5	<20	423	0.24	<10	176	<10	3	63
41	S07-19067	0.4	8.01	5	575	<5	3.63	<1	20	73	115	5.42	1.13	<10	1.84	1225	<1	3.28	16	770	34	<5	<20	455	0.23	<10	219	<10	3	59
42	S07-19068	0.2	7.84	15	550	<5	4.60	<1	21	139	83	6.16	1.12	<10	2.97	1191	<1	2.05	38	890	32	<5	<20	494	0.24	<10	189	<10	6	59
43	S07-19069	0.2	7.47	15	795	<5	3.80	<1	22	164	39	5.11	1.02	10	2.79	975	<1	2.21	38	860	28	<5	<20	336	0.24	<10	192	<10	9	60
44	S07-19070	0.6	7.25	<5	295	<5	2.60	<1	13	118	92	4.17	1.17	10	1.79	755	<1	3.96	18	800	46	<5	<20	297	0.24	<10	133	<10	6	68
45	S07-19071	0.6	7.19	15	560	<5	3.86	<1	19	149	31	4.59	1.44	10	2.11	929	<1	2.80	29	860	30	<5	<20	372	0.24	<10	169	<10	10	55
46	S07-19072	0.6	7.75	10	670	<5	2.86	<1	16	126	62	4.53	1.47	10	1.86	979	<1	3.03	22	880	26	<5	<20	398	0.19	<10	146	<10	5	64
47	S07-19073	0.2	6.66	10	505	<5	2.29	<1	13	205	50	4.03	1.19	10	1.42	863	<1	3.24	17	770	28	<5	<20	420	0.17	<10	119	<10	5	49
48	S07-19074	0.6	7.09	<5	615	<5	2.05	<1	8	90	86	3.92	1.12	10	1.43	960	<1	2.28	13	870	28	<5	<20	251	0.21	<10	123	<10	5	41
49	S07-19075	6.0	3.90	140	370	<5	0.40	<1	7	43	59	3.34	2.94	<10	0.29	222	6	0.50	22	410	22	65	<20	93	0.28	<10	42	<10	10	51
50	S07-19076	0.4	7.47	5	365	<5	2.31	<1	11	67	40	4.36	1.32	10	1.65	882	<1	3.23	15	860	30	<5	<20	259	0.22	<10	142	<10	6	65
51	S07-19077	0.4	7.06	10	610	<5	3.37	<1	18	114	61	4.62	1.16	10	2.08	1042	<1	1.74	28	870	28	<5	<20	329	0.22	<10	181	<10	6	50
52	S07-19078	<0.2	7.51	15	730	<5	3.41	<1	22	98	54	4.82	1.24	10	2.57	1096	<1	2.22	33	910	28	<5	<20	326	0.24	<10	229	<10	7	54
53	S07-19079	0.4	7.28	10	765	<5	3.82	<1	26	133	90	5.59	1.52	10	2.93	1135	<1	1.68	50	880	30	<5	<20	333	0.23	<10	209	<10	8	66
54	S07-19080	0.2	7.00	15	715	<5	6.22	<1	24	106	62	5.49	1.59	<10	2.85	1262	<1	2.44	45	1060	24	<5	<20	510	0.16	<10	210	<10	7	52
55	S07-19081	0.8	7.81	10	540	<5	4.54	<1	24	70	112	5.95	1.27	<10	2.66	1222	<1	3.39	34	1050	26	<5	<20	501	0.22	<10	243	<10	5	60
56	S07-19082	0.4	7.63	15	530	<5	4.29	<1	20	49	102	5.40	1.17	<10	2.34	1082	<1	2.96	26	910	32	<5	<20	531	0.21	<10	244	<10	5	54
57	S07-19083	0.8	8.17	10	685	<5	5.42	1	21	59	152	5.77	1.62	<10	2.49	1294	<1	2.90	28	1010	142	<5	<20	733	0.21	<10	234	<10	6	189
58	S07-19084	0.4	8.17	15	710	<5	4.52	<1	22	49	75	6.04	1.29	10	2.54	1213	<1	2.63	26	990	28	<5	<20	564	0.25	<10	254	<10	5	51
59	S07-19085	0.6	7.98	10	780	<5	3.89	1	23	58	84	5.96	1.33	<10	2.38	1169	<1	2.85	29	940	34	<5	<20	476	0.22	<10	252	<10	5	141
60	S07-19086	0.4	8.42	15	1055	<5	3.70	<1	22	153	61	5.89	1.36	10	2.29	1142	<1	2.09	26	1120	34	<5	<20	432	0.26	<10	221	<10	5	46
61	S07-19087	0.4	6.98	10	505	<5	2.61	<1	16	147	56	4.48	1.38	10	1.77	814	<1	4.00	22	950	24	<5	<20	443	0.22	<10	143	<10	4	60
62	S07-19088	0.2	7.26	15	470	<5	3.09	<1	17	185	62	4.45	1.36	10	1.76	888	<1	3.99	27	910	28	<5	<20	438	0.23	<10	169	<10	5	49
63	S07-19089	0.2	7.04	10	910	<5	2.30	<1	15	335	48	4.35	1.09	10	1.65	858	1	2.59	28	820	22	<5	<20	359	0.18	<10	167	<10	4	48
64	S07-19090	0.4	7.97	5	1520	<5	2.96	<1	16	158	98	4.68	1.20	10	1.73	953	<1	3.38	24	900	30	<5	<20	457	0.22	<10	168	<10	5	62
65	S07-19091	0.2	6.96	5	885	<5	2.80	<1	15	105	54	4.03	0.97	10	1.41	847	<1	4.22	19	770	34	<5	<20	414	0.28	<10	156	<10	6	54

It #.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
66	S07-19092	<0.2	7.33	10	970	<5	3.02	<1	14	101	76	4.16	1.22	10	1.51	886	<1	4.09	18	820	28	<5	<20	455	0.25	<10	161	<10	6	62
67	S07-19093	0.2	7.19	25	825	<5	2.28	<1	16	147	44	4.56	0.97	10	1.56	936	<1	4.29	21	870	28	<5	<20	379	0.28	<10	168	<10	5	54
68	S07-19094	0.4	7.10	10	1045	<5	3.21	<1	15	118	63	4.02	0.91	10	1.52	803	<1	3.84	18	860	32	<5	<20	488	0.29	<10	158	<10	8	47
69	S07-19095	0.2	7.58	15	975	<5	3.24	<1	20	120	63	5.34	0.87	10	2.28	1009	<1	3.61	31	950	62	<5	<20	522	0.29	<10	198	<10	8	94
70	S07-19096	0.4	7.59	15	835	<5	3.88	<1	24	117	75	5.94	0.92	10	2.65	1183	<1	2.91	43	1020	28	<5	<20	505	0.29	<10	248	<10	7	65
71	S07-19097	0.8	7.76	15	645	<5	3.40	<1	25	112	108	6.21	0.85	10	2.44	1079	<1	3.13	42	1160	66	<5	<20	468	0.30	<10	288	<10	7	80
72	S07-19098	0.4	8.21	15	690	<5	4.25	<1	22	116	56	6.14	1.07	20	2.30	1150	<1	3.14	39	1420	56	<5	<20	537	0.32	<10	255	<10	9	69
73	S07-19099	0.8	7.57	15	645	<5	4.46	<1	21	97	126	5.41	1.00	20	2.10	933	2	3.76	37	1540	30	<5	<20	505	0.28	<10	211	<10	11	72
74	S07-19100	0.4	7.09	15	905	<5	3.63	<1	27	134	120	5.88	0.94	10	3.15	1058	<1	3.08	55	1200	24	<5	<20	349	0.21	<10	251	<10	8	71
75	S07-19101	<0.2	0.05	<5	15	<5	>10	<1	<1	<1	<1	0.04	<0.01	<10	1.80	26	<1	0.01	20	40	<2	<5	<20	5881	<0.01	<10	3	<10	<1	1
76	S07-19102	0.4	7.24	20	465	<5	3.35	<1	28	178	69	6.26	1.08	10	3.88	1156	<1	3.08	70	1220	24	<5	<20	339	0.13	<10	242	<10	7	64
77	S07-19103	0.2	6.92	25	460	<5	3.70	<1	30	247	64	6.34	0.89	<10	4.49	1296	<1	2.10	96	1140	24	<5	<20	340	0.12	<10	247	<10	7	51
78	S07-19104	0.2	7.19	20	345	<5	4.28	<1	28	251	89	5.66	1.21	10	3.86	1142	<1	2.86	94	1130	26	<5	<20	386	0.12	<10	235	<10	8	52
79	S07-19105	0.2	7.00	20	295	<5	3.66	<1	24	278	98	5.44	0.93	20	3.61	945	<1	3.10	87	1310	26	<5	<20	353	0.14	<10	168	<10	9	53
80	S07-19106	0.2	7.15	25	585	<5	3.27	<1	32	314	106	6.19	1.01	10	4.28	1161	<1	2.31	104	1060	24	<5	<20	340	0.13	<10	215	<10	7	68
81	S07-19107	0.2	8.00	15	1320	<5	3.25	<1	25	84	73	5.68	0.96	10	3.04	1091	<1	3.14	37	1180	26	<5	<20	380	0.28	<10	234	<10	8	55
82	S07-19108	0.2	7.89	10	1925	<5	4.20	<1	21	125	45	5.50	0.99	10	3.34	1531	<1	2.16	36	1070	28	<5	<20	497	0.22	<10	232	<10	8	45
83	S07-19109	<0.2	7.72	15	2540	<5	4.18	<1	19	110	62	5.59	1.07	10	3.28	1541	<1	2.63	38	1400	24	<5	<20	429	0.24	<10	232	<10	10	57
84	S07-19110	<0.2	7.53	10	2275	<5	4.24	<1	19	107	43	4.78	0.97	10	2.67	1466	<1	2.62	32	1050	32	<5	<20	557	0.27	<10	193	<10	9	49
85	S07-19111	4.5	4.49	120	210	<5	0.50	1	11	33	572	5.08	2.46	10	1.73	386	7	0.27	25	530	106	50	<20	71	0.28	<10	55	<10	11	657
86	S07-19112	0.4	6.08	15	2170	<5	4.32	<1	18	286	90	4.60	1.05	10	2.56	1606	<1	0.95	31	1310	58	<5	<20	554	0.23	<10	157	<10	9	141
87	S07-19113	0.4	6.74	15	1880	<5	1.51	1	12	176	80	3.80	1.36	20	2.09	1028	2	0.19	46	530	28	<5	<20	188	0.21	<10	228	<10	6	172
88	S07-19114	<0.2	6.52	5	1940	<5	1.62	1	5	194	32	3.41	1.28	20	1.90	1121	2	0.17	32	500	20	<5	<20	213	0.15	<10	205	<10	6	142
89	S07-19115	<0.2	7.11	15	2020	<5	1.92	<1	8	216	17	3.49	1.14	20	1.91	1156	<1	0.19	33	1490	20	<5	<20	241	0.15	<10	156	<10	9	85
90	S07-19116	<0.2	6.94	10	1970	<5	2.20	<1	7	147	16	3.51	1.73	20	1.94	1239	<1	0.18	32	1760	22	<5	<20	264	0.14	<10	152	<10	9	95
91	S07-19117	<0.2	5.14	25	310	<5	2.52	<1	9	153	65	2.62	1.04	20	1.24	1327	7	0.15	61	540	20	<5	<20	309	0.16	<10	130	<10	7	100
92	S07-19118	0.8	5.06	35	405	<5	2.61	<1	11	269	83	2.79	1.08	20	1.34	1859	5	0.13	106	450	22	<5	<20	314	0.16	<10	127	<10	6	145
93	S07-19119	0.8	5.76	65	1330	<5	1.54	1	20	292	156	3.53	1.18	20	1.58	2958	2	0.14	204	420	24	<5	<20	199	0.19	<10	115	<10	5	210
94	S07-19120	0.8	5.91	50	720	<5	2.19	<1	18	299	97	3.32	1.04	30	1.57	3667	<1	0.17	161	440	30	<5	<20	280	0.22	<10	99	<10	6	103
95	S07-19121	1.0	6.02	45	750	<5	1.42	<1	22	108	175	3.78	1.10	30	1.79	2793	1	0.16	170	450	26	<5	<20	204	0.21	<10	97	<10	5	144
96	S07-19122	0.8	4.47	35	865	<5	2.25	<1	15	263	67	3.24	1.00	20	1.78	4037	1	0.10	131	410	20	<5	<20	360	0.16	<10	82	<10	6	131
97	S07-19123	1.0	5.40	30	1015	<5	1.30	<1	17	427	95	3.34	1.16	20	1.77	2647	<1	0.14	160	470	24	<5	<20	184	0.20	<10	94	<10	6	110
98	S07-19124	0.6	5.27	30	1030	<5	1.27	<1	15	222	78	3.32	1.00	20	1.94	3050	<1	0.18	189	430	24	<5	<20	181	0.21	<10	90	<10	6	107
99	S07-19125	0.6	4.78	40	885	<5	1.67	<1	16	229	62	3.13	0.96	20	1.90	3650	<1	0.20	195	410	24	<5	<20	221	0.20	<10	90	<10	6	141
00	S07-19126	1.0	4.24	40	820	<5	1.84	<1	20	188	67	2.92	0.92	20	1.91	3764	<1	0.18	201	380	20	<5	<20	246	0.19	<10	85	<10	5	218
01	S07-19127	0.8	4.62	55	860	<5	2.35	<1	21	169	110	3.28	0.87	20	1.99	4629	1	0.19	266	400	26	<5	<20	299	0.18	<10	88	<10	6	161
02	S07-19128	0.6	4.90	60	890	<5	1.80	<1	14	159	87	3.07	0.90	20	2.04	3795	<1	0.19	162	430	22	<5	<20	251	0.19	<10	88	<10	5	109
03	S07-19129	0.6	4.43	25	765	<5	2.51	<1	12	156	81	3.21	0.92	20	2.07	3869	<1	0.13	104	510	50	<5	<20	340	0.15	<10	76	<10	6	176
04	S07-19130	1.0	5.01	30	900	<5	1.07	<1	14	162	163	3.04	1.03	20	1.71	2321	<1	0.14	95	390	38	<5	<20	167	0.19	<10	83	<10	5	162
05	S07-19131	0.9	5.65	125	175	<5	0.27	<1	8	24	30	3.65	4.43	10	0.34	160	3	0.08	15	480	16	40	<20	50	0.37	<10	71	<10	10	46

It #.	Sample	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	V	W	Y	Zn			
106	S07-19132	1.0	4.78	35	870	<5	1.74	<1	16	161	74	3.22	1.98	20	1.96	3159	<1	0.11	154	420	40	<5	<20	258	0.18	<10	92	<10	7	141
107	S07-19133	1.0	4.26	30	770	<5	1.37	<1	12	168	77	2.67	1.98	20	1.73	2534	<1	0.19	98	400	28	<5	<20	226	0.17	<10	80	<10	6	119
108	S07-19134	0.8	4.68	25	825	<5	1.70	<1	13	221	114	2.71	2.10	20	1.75	2535	<1	0.22	89	410	32	<5	<20	253	0.17	<10	80	<10	6	119
109	S07-19135	1.0	5.47	35	910	<5	2.26	<1	14	201	100	3.11	2.20	30	2.04	3199	<1	0.41	171	590	34	<5	<20	317	0.20	<10	95	<10	10	137
110	S07-19136	0.6	5.97	25	1040	<5	1.32	<1	17	139	116	3.38	2.50	20	1.88	2852	<1	0.44	137	460	30	<5	<20	191	0.24	<10	97	<10	8	101
111	S07-19137	0.8	6.58	35	1175	<5	1.04	<1	22	167	129	3.73	2.58	30	1.67	3491	<1	0.57	190	560	36	<5	<20	154	0.25	<10	104	<10	8	105
112	S07-19138	1.2	6.73	35	1155	<5	1.28	<1	18	188	241	3.86	2.61	30	1.95	4195	<1	0.45	174	550	102	<5	<20	195	0.25	<10	103	<10	8	170
113	S07-19139	0.8	4.34	30	1070	<5	1.86	<1	13	247	58	2.53	1.77	20	1.53	2566	<1	0.12	84	350	20	<5	<20	211	0.17	<10	71	<10	7	74
114	S07-19140	1.2	5.52	40	870	<5	2.00	<1	19	300	132	2.77	2.20	30	1.47	1461	2	0.38	129	470	24	<5	<20	241	0.19	<10	96	<10	8	110
115	S07-19141	0.6	3.59	<5	475	<5	2.57	<1	5	137	16	1.51	1.17	20	0.98	1612	<1	0.94	18	520	60	<5	<20	269	0.16	<10	34	<10	6	49
116	S07-19142	0.4	4.63	15	840	<5	3.42	<1	8	188	39	1.93	1.84	20	1.38	1325	<1	0.66	65	430	20	<5	<20	320	0.16	<10	62	<10	8	56
117	S07-19143	0.4	4.05	10	810	<5	3.11	<1	6	209	56	1.87	1.60	20	1.26	1090	<1	0.70	36	430	16	<5	<20	307	0.14	<10	62	<10	7	80
118	S07-19144	<0.2	4.12	5	720	<5	2.95	<1	4	126	39	1.64	1.60	20	1.20	1011	1	0.70	32	450	12	<5	<20	294	0.16	<10	62	<10	6	46
119	S07-19145	1.4	5.35	25	570	<5	3.34	<1	27	308	182	4.58	2.22	20	1.62	1748	9	0.57	198	710	38	5	<20	353	0.15	<10	180	<10	8	210

DATA:

Lead:

1	S07-19027	<0.2	9.03	<5	230	<5	3.79	<1	19	37	74	5.54	0.42	10	2.30	1086	<1	4.16	24	1020	36	<5	<20	457	0.42	<10	219	<10	18	73
20	S07-19046	0.2	5.12	10	425	<5	2.82	<1	10	257	25	3.57	1.28	10	0.89	728	<1	1.32	13	870	24	<5	<20	316	0.17	<10	82	<10	9	53
36	S07-19062	0.4	6.96	<5	600	<5	2.50	<1	12	198	66	3.58	1.46	20	1.21	853	<1	2.17	13	830	28	<5	<20	304	0.18	<10	108	<10	6	66
35	S07-19071	0.7	7.22	10	555	<5	3.84	<1	19	142	31	4.75	1.53	10	2.11	937	<1	2.79	30	860	30	<5	<20	371	0.25	<10	170	<10	8	56
4	S07-19080	0.2	7.12	25	740	<5	6.27	<1	26	108	64	5.63	1.46	10	2.97	1265	<1	2.40	44	1050	24	<5	<20	519	0.19	<10	219	<10	7	50
71	S07-19097	0.8	7.64	15	645	<5	3.42	<1	24	110	106	6.08	1.04	10	2.44	1065	<1	3.11	41	1130	64	<5	<20	465	0.29	<10	287	<10	8	80
80	S07-19106	0.2	7.28	25	580	<5	3.46	<1	34	305	107	6.29	1.04	10	4.27	1176	<1	2.32	108	1070	22	<5	<20	336	0.14	<10	213	<10	7	70
9	S07-19115	<0.2	7.15	10	2020	<5	1.97	<1	7	226	16	3.54	1.17	20	1.89	1163	1	0.20	33	1500	22	<5	<20	241	0.15	<10	155	<10	9	85
86	S07-19132	1.1	4.81	25	840	<5	1.80	<1	16	174	73	3.24	2.10	20	1.93	3168	<1	0.11	148	410	37	<5	<20	254	0.18	<10	90	<10	7	131

Alit:


1	S07-19027	0.2	8.40	<5	215	<5	3.36	<1	18	42	72	5.38	0.38	10	2.24	1042	<1	3.95	22	970	32	<5	<20	440	0.38	<10	208	<10	17	69
6	S07-19062	0.4	7.05	10	610	<5	2.60	<1	10	169	70	3.76	0.98	20	1.20	876	<1	2.12	12	790	24	<5	<20	315	0.19	<10	112	<10	6	60
1	S07-19097	0.8	7.34	15	590	<5	3.31	<1	28	110	104	6.09	0.93	10	2.35	1038	1	3.15	45	1090	62	<5	<20	471	0.28	<10	264	<10	7	74
16	S07-19132	0.8	4.41	30	775	<5	1.88	<1	15	177	65	3.18	2.01	20	1.93	3227	<1	0.12	142	430	35	<5	<20	270	0.16	<10	81	<10	6	120


Standard:

3		0.5	5.89	25	1295	<5	2.35	<1	15	60	36	4.19	1.39	40	1.40	2559	5	1.13	30	1650	58	<5	<20	255	0.33	<10	109	<10	29	198
3		0.5	5.61	26	1310	<5	2.44	<1	15	60	37	4.05	1.40	40	1.41	2519	5	1.16	30	1650	54	<5	<20	267	0.32	<10	109	<10	29	201
3		0.4	5.88	25	1255	<5	2.40	<1	16	58	38	4.14	1.33	40	1.36	2603	5	1.16	31	1680	60	<5	<20	250	0.36	<10	122	<10	29	193
3		0.5	5.76	25	1260	<5	2.35	<1	16	59	34	4.19	1.39	30	1.35	2573	5	1.16	30	1670	60	<5	<20	261	0.35	<10	122	<10	28	192

4 ACID DIGEST/ICP-FINISH
4 ACID DIGEST/AA-FINISH

282S
07


ECO TECH LABORATORY LTD.
Jutta Jehliouse
B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2283

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

5-Mar-08

Attention: Bob Singh

No. of samples received: 256

Sample Type: Core

Project: Spanish Mountain


Shipment #: SMC-07-155

Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-19146	<0.03	<0.001
2	S07-19147	<0.03	<0.001
3	S07-19148	<0.03	<0.001
4	S07-19149	<0.03	<0.001
5	S07-19150	<0.03	<0.001
6	S07-19151	<0.03	<0.001
7	S07-19152	<0.03	<0.001
8	S07-19153	<0.03	<0.001
9	S07-19154	<0.03	<0.001
10	S07-19155	<0.03	<0.001
11	S07-19156	<0.03	<0.001
12	S07-19157	<0.03	<0.001
13	S07-19158	<0.03	<0.001
14	S07-19159	<0.03	<0.001
15	S07-19160	<0.03	<0.001
16	S07-19161	<0.03	<0.001
17	S07-19162	<0.03	<0.001
18	S07-19163	<0.03	<0.001
19	S07-19164	<0.03	<0.001
20	S07-19165	<0.03	<0.001
21	S07-19166	<0.03	<0.001
22	S07-19167	<0.03	<0.001
23	S07-19168	<0.03	<0.001
24	S07-19169	<0.03	<0.001
25	S07-19170	<0.03	<0.001
26	S07-19171	<0.03	<0.001
27	S07-19172	<0.03	<0.001
28	S07-19173	<0.03	<0.001
29	S07-19174	0.52	0.015
30	S07-19175	0.06	0.002

* = 30g FA


ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
31	S07-19176	<0.03	<0.001
32	S07-19177	0.35	0.010
33	S07-19178	<0.03	<0.001
34	S07-19179	<0.03	<0.001
35	S07-19180	<0.03	<0.001
36	S07-19181	<0.03	<0.001
37	S07-19182	<0.03	<0.001
38	S07-19183	* 6.67	0.195
39	S07-19184	0.03	0.001
40	S07-19185	<0.03	<0.001
41	S07-19186	<0.03	<0.001
42	S07-19187	<0.03	<0.001
43	S07-19188	<0.03	<0.001
44	S07-19189	<0.03	<0.001
45	S07-19190	<0.03	<0.001
46	S07-19191	<0.03	<0.001
47	S07-19192	<0.03	<0.001
48	S07-19193	<0.03	<0.001
49	S07-19194	<0.03	<0.001
50	S07-19195	0.09	0.003
51	S07-19196	0.05	0.002
52	S07-19197	<0.03	<0.001
53	S07-19198	<0.03	<0.001
54	S07-19199	<0.03	<0.001
55	S07-19200	<0.03	<0.001
56	S07-19201	<0.03	<0.001
57	S07-19202	0.05	0.002
58	S07-19203	<0.03	<0.001
59	S07-19204	<0.03	<0.001
60	S07-19205	<0.03	<0.001
61	S07-19206	<0.03	<0.001
62	S07-19207	* <0.03	<0.001
63	S07-19208	<0.03	<0.001
64	S07-19209	0.10	0.003
65	S07-19210	<0.03	<0.001
66	S07-19211	<0.03	<0.001
67	S07-19212	<0.03	<0.001
68	S07-19213	* 2.08	0.061
69	S07-19214	<0.03	<0.001
70	S07-19215	<0.03	<0.001
71	S07-19216	<0.03	<0.001
72	S07-19217	<0.03	<0.001
73	S07-19218	<0.03	<0.001

* = 30g FA

Dyanne Bruce
ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
74	S07-19219	<0.03	<0.001
75	S07-19220	<0.03	<0.001
76	S07-19221	<0.03	<0.001
77	S07-19222	<0.03	<0.001
78	S07-19223	<0.03	<0.001
79	S07-19224	0.09	0.003
80	S07-19225	<0.03	<0.001
81	S07-19226	<0.03	<0.001
82	S07-19227	0.13	0.004
83	S07-19228	0.03	0.001
84	S07-19229	0.15	0.004
85	S07-19230	<0.03	<0.001
86	S07-19231	<0.03	<0.001
87	S07-19232	<0.03	<0.001
88	S07-19233	<0.03	<0.001
89	S07-19234	<0.03	<0.001
90	S07-19235	<0.03	<0.001
91	S07-19236	<0.03	<0.001
92	S07-19237	<0.03	<0.001
93	S07-19238	<0.03	<0.001
94	S07-19239	<0.03	<0.001
95	S07-19240	*	<0.03
96	S07-19241	<0.03	<0.001
97	S07-19242	<0.03	<0.001
98	S07-19243	0.04	0.001
99	S07-19244	0.05	0.001
100	S07-19245	0.04	0.001
101	S07-19246	<0.03	<0.001
102	S07-19247	<0.03	<0.001
103	S07-19248	<0.03	<0.001
104	S07-19249	<0.03	<0.001
105	S07-19250	<0.03	<0.001
106	S07-19251	*	0.44
107	S07-19252	<0.03	<0.001
108	S07-19253	<0.03	<0.001
109	S07-19254	0.03	0.001
110	S07-19255	0.03	0.001
111	S07-19256	<0.03	<0.001
112	S07-19257	<0.03	<0.001
113	S07-19258	<0.03	<0.001
114	S07-19259	<0.03	<0.001
115	S07-19260	<0.03	<0.001
116	S07-19261	<0.03	<0.001

* = 30g FA

Stuart Bruce
ECO TECH LABORATORY LTD.
 Jutta Jealousie
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
117	S07-19262	<0.03	<0.001
118	S07-19263	<0.03	<0.001
119	S07-19264	<0.03	<0.001
120	S07-19265	<0.03	<0.001
121	S07-19266	<0.03	<0.001
122	S07-19267	<0.03	<0.001
123	S07-19268	<0.03	<0.001
124	S07-19269	<0.03	<0.001
125	S07-19270	<0.03	<0.001
126	S07-19271	<0.03	<0.001
127	S07-19272	*	<0.03
128	S07-19273	<0.03	<0.001
129	S07-19274	<0.03	<0.001
130	S07-19275	<0.03	<0.001
131	S07-19276	<0.03	<0.001
132	S07-19277	<0.03	<0.001
133	S07-19278	<0.03	<0.001
134	S07-19279	<0.03	<0.001
135	S07-19280	<0.03	<0.001
136	S07-19281	<0.03	<0.001
137	S07-19282	*	6.60
138	S07-19283	<0.03	<0.001
139	S07-19284	<0.03	<0.001
140	S07-19285	0.21	0.006
141	S07-19286	<0.03	<0.001
142	S07-19287	<0.03	<0.001
143	S07-19288	<0.03	<0.001
144	S07-19289	<0.03	<0.001
145	S07-19290	<0.03	<0.001
146	S07-19291	<0.03	<0.001
147	S07-19292	0.10	0.003
148	S07-19293	0.05	0.001
149	S07-19294	<0.03	<0.001
150	S07-19295	<0.03	<0.001
151	S07-19296	0.04	0.001
152	S07-19297	<0.03	<0.001
153	S07-19298	<0.03	<0.001
154	S07-19299	0.25	0.007
155	S07-19300	0.54	0.016
156	S07-19301	*	<0.03
157	S07-19302	1.40	0.041
158	S07-19303	0.77	0.023
159	S07-19304	0.65	0.019

* = 30g FA

John Bruce Jones
ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
160	S07-19305	0.25	0.007
161	S07-19306	0.39	0.011
162	S07-19307	0.53	0.015
163	S07-19308	0.43	0.012
164	S07-19309	0.16	0.005
165	S07-19310	0.16	0.005
166	S07-19311	0.12	0.003
167	S07-19312	0.04	0.001
168	S07-19313	<0.03	<0.001
169	S07-19314	0.05	0.002
170	S07-19315	<0.03	<0.001
171	S07-19316	<0.03	<0.001
172	S07-19317	<0.03	<0.001
173	S07-19318	2.02	0.059
174	S07-19319	<0.03	<0.001
175	S07-19320	0.03	0.001
176	S07-19321	<0.03	<0.001
177	S07-19322	<0.03	<0.001
178	S07-19323	<0.03	<0.001
179	S07-19324	<0.03	<0.001
180	S07-19325	0.28	0.008
181	S07-19326	<0.03	<0.001
182	S07-19327	0.01	0.000
183	S07-19328	0.14	0.004
184	S07-19329	<0.03	<0.001
185	S07-19330	<0.03	<0.001
186	S07-19331	<0.03	<0.001
187	S07-19332	0.08	0.002
188	S07-19333	0.11	0.003
189	S07-19334	0.04	0.001
190	S07-19335	0.28	0.008
191	S07-19336	<0.03	<0.001
192	S07-19337	<0.03	<0.001
193	S07-19338	0.03	0.001
194	S07-19339	<0.03	<0.001
195	S07-19340	<0.03	<0.001
196	S07-19341	<0.03	<0.001
197	S07-19342	<0.03	<0.001
198	S07-19343	0.11	0.003
199	S07-19344	<0.03	<0.001
200	S07-19345	0.24	0.007
201	S07-19346	0.09	0.003
202	S07-19347	0.05	0.002

* = 30g FA

Alan Bruce
ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
203	S07-19348	<0.03	<0.001
204	S07-19349	0.13	0.004
205	S07-19350	0.07	0.002
206	S07-19351	<0.03	<0.001
207	S07-19352	0.05	0.002
208	S07-19353	0.81	0.024
209	S07-19354	* 0.41	0.012
210	S07-19355	0.57	0.017
211	S07-19356	0.40	0.012
212	S07-19357	0.12	0.004
213	S07-19358	0.18	0.005
214	S07-19359	0.30	0.009
215	S07-19360	0.89	0.026
216	S07-19361	0.09	0.003
217	S07-19362	0.16	0.005
218	S07-19363	0.07	0.002
219	S07-19364	0.32	0.009
220	S07-19365	0.11	0.003
221	S07-19366	0.10	0.003
222	S07-19367	0.48	0.014
223	S07-19368	0.26	0.007
224	S07-19369	0.11	0.003
225	S07-19370	0.13	0.004
226	S07-19371	0.07	0.002
227	S07-19372	* <0.03	<0.001
228	S07-19373	0.38	0.011
229	S07-19374	0.46	0.013
230	S07-19375	0.17	0.005
231	S07-19376	0.15	0.005
232	S07-19377	0.28	0.008
233	S07-19378	0.07	0.002
234	S07-19379	0.14	0.004
235	S07-19380	0.87	0.025
236	S07-19381	22.2	0.647
237	S07-19382	0.75	0.022
238	S07-19383	0.62	0.018
239	S07-19384	0.24	0.007
240	S07-19385	0.32	0.009
241	S07-19386	0.42	0.012
242	S07-19387	0.13	0.004
243	S07-19388	0.36	0.010
244	S07-19389	0.23	0.007
245	S07-19390	* 2.09	0.061

* = 30g FA

Jutta Jealouse
ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
246	S07-19391	0.18	0.005
247	S07-19392	0.92	0.027
248	S07-19393	0.06	0.002
249	S07-19394	0.09	0.003
250	S07-19395	0.06	0.002
251	S07-19396	0.06	0.002
252	S07-19397	0.17	0.005
253	S07-19398	0.10	0.003
254	S07-19399	0.23	0.007
255	S07-19400	0.05	0.001
256	S07-19401	1.03	0.030

QC DATA:**Resplit:**

1	S07-19146	<0.03	<0.001
36	S07-19181	<0.03	<0.001
71	S07-19216	<0.03	<0.001
106	S07-19251	<0.03	<0.001
141	S07-19286	<0.03	<0.001
176	S07-19321	<0.03	<0.001
211	S07-19356	0.56	0.016
246	S07-19391	0.13	0.004

Standard:

OXI54	1.84	0.054
OXI54	1.86	0.054
OXI54	1.90	0.055
OXI54	1.84	0.054
OXI54	1.86	0.054
OXI54	1.88	0.055
OXI54	1.90	0.055
OXI54	1.86	0.054
OXI54	1.88	0.055
OXI54	1.82	0.053
OXI54	1.88	0.055
OXI54	1.87	0.055
OXI54	1.84	0.054
OXI54	1.80	0.052
OXI54	1.80	0.052
OXI54	1.83	0.053
OXI54	1.82	0.053
OXI54	1.86	0.054

* = 30g FA

Jutta Jealouse
ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays


ET #.	Tag #	Au (g/t)	Au (oz/t)
OXI54		1.80	0.052
OXI54		1.86	0.054
OXI54		1.82	0.053
OXI54		1.88	0.055

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw

XLS/07


ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

TECH LABORATORY LTD.
 11 Dallas Drive
 ILOOPS, B.C.
 6T4

ICP CERTIFICATE OF ANALYSIS 2007-2284

Skygold Ventures
 615 - 800 W. Pender Street
 Vancouver, BC
 V6B 2V6

Phone: 250-573-5700
 Fax: 250-573-4557

No. of samples received: 5
 Sample Type: Core
 Project: Spanish Mountain
 Shipment #: SMC-07-153
 Samples submitted by: Tasha Gainer

Concentrations in ppm unless otherwise reported

#.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-19022	<0.2	8.25	<5	785	<5	3.02	<1	14	68	74	4.14	1.42	10	1.81	969	<1	3.03	16	980	30	<5	<20	358	0.26	<10	159	<10	11	66
2	S07-19023	<0.2	8.86	<20	825	<5	3.55	<1	21	58	115	5.49	1.40	10	2.29	1098	<1	3.38	22	940	32	<5	<20	372	0.28	<10	212	<10	9	80
3	S07-19024	0.2	8.99	<5	335	<5	4.09	<1	18	67	100	5.30	0.59	10	2.32	1158	<1	3.77	21	960	34	<5	<20	461	0.39	<10	196	<10	16	74
4	S07-19025	0.2	8.59	<5	385	<5	4.31	<1	18	99	64	5.17	0.77	10	2.37	1145	<1	3.32	23	910	34	<5	<20	451	0.36	<10	218	<10	15	70
5	S07-19026	<0.2	8.89	<5	235	<5	4.09	<1	19	73	90	5.17	0.46	10	2.28	1147	<1	3.87	23	980	34	<5	<20	476	0.41	<10	205	<10	17	69

DATA:

Heat:

1	S07-19022	0.2	8.51	<5	780	<5	3.05	<1	14	60	76	4.24	1.40	10	1.82	989	<1	2.96	16	1010	30	<5	<20	356	0.29	<10	159	<10	11	65
---	-----------	-----	------	----	-----	----	------	----	----	----	----	------	------	----	------	-----	----	------	----	------	----	----	-----	-----	------	-----	-----	-----	----	----

Split:


1	S07-19022	<0.2	8.34	<5	760	<5	3.14	<1	13	60	67	4.13	1.37	10	1.67	988	<1	2.93	16	990	30	<5	<20	355	0.30	<10	146	<10	12	68
---	-----------	------	------	----	-----	----	------	----	----	----	----	------	------	----	------	-----	----	------	----	-----	----	----	-----	-----	------	-----	-----	-----	----	----


Standard:

13		0.4	5.83	20	1300	<5	2.81	<1	16	60	35	4.09	1.64	30	1.43	2725	5	1.16	34	1860	62	<5	<20	273	0.34	<10	113	<10	29	193
----	--	-----	------	----	------	----	------	----	----	----	----	------	------	----	------	------	---	------	----	------	----	----	-----	-----	------	-----	-----	-----	----	-----

4 ACID DIGEST/ICP-FINISH
 4 ACID DIGEST/AA-FINISH

HW
 2275s
 3/07


 ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2284

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

5-Mar-08

Attention: Bob Singh

No. of samples received: 5
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-153
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-19022	<0.03	<0.001
2	S07-19023	<0.03	<0.001
3	S07-19024	<0.03	<0.001
4	S07-19025	<0.03	<0.001
5	S07-19026	<0.03	<0.001

QC DATA:

Resplit:

1	S07-19022	0.03	0.001
---	-----------	------	-------

Standard:

OXI54	1.90	0.055
-------	------	-------

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

JJ/nw
XLS/07


ECOTECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

5-Mar-08

ECO TECH LABORATORY LTD.

10041 Dallas Drive
KAMLOOPS, B.C.
 V2C 6T4

Phone: 250-573-5700
 Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2007-2283

Skygold Ventures
 615 - 800 W. Pender Street
Vancouver, BC
 V6B 2V6

No. of samples received: 256

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-155

Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Z
1	S07-19146	0.2	5.09	5	1710	<5	0.71	<1	3	49	21	1.76	1.89	10	1.09	1964	<1	0.71	12	240	22	<5	<20	79	0.11	<10	29	<10	8	7
2	S07-19147	0.2	6.36	10	1925	<5	0.82	<1	6	228	21	2.36	2.29	20	1.36	1779	<1	1.00	20	350	28	<5	<20	91	0.16	<10	25	<10	13	7
3	S07-19148	0.2	6.13	35	1390	<5	1.37	<1	14	200	140	2.84	1.94	20	1.70	1734	<1	0.87	43	380	32	<5	<20	115	0.11	<10	46	<10	8	5
4	S07-19149	0.4	4.80	60	890	<5	2.90	<1	30	643	54	4.62	1.52	10	3.56	2928	2	0.44	190	700	30	5	<20	238	0.09	<10	92	<10	6	11
5	S07-19150	0.2	7.93	5	535	<5	3.25	<1	11	47	39	4.28	1.15	10	1.45	871	3	3.02	30	890	32	<5	<20	409	0.40	<10	117	<10	19	5
6	S07-19151	0.4	5.34	30	1630	<5	1.52	<1	9	274	14	2.24	1.91	20	1.68	1437	<1	0.29	47	300	34	<5	<20	122	0.10	<10	60	<10	8	5
7	S07-19152	0.4	5.75	<5	1620	<5	1.04	<1	5	174	34	2.03	2.08	10	1.29	1463	<1	0.67	14	340	28	<5	<20	105	0.13	<10	35	<10	7	5
8	S07-19153	0.6	4.96	35	830	<5	2.91	<1	30	602	73	3.29	1.98	10	4.82	1427	<1	0.28	231	520	20	5	<20	209	0.06	<10	62	<10	6	5
9	S07-19154	0.2	5.09	60	755	<5	3.41	<1	33	576	32	3.42	1.62	20	4.05	1964	<1	0.25	217	550	32	5	<20	201	0.10	<10	73	<10	9	6
10	S07-19155	0.4	6.16	10	1810	<5	1.00	<1	12	81	77	2.82	1.99	20	2.11	2688	<1	0.39	27	630	32	<5	<20	97	0.14	<10	82	<10	9	8
11	S07-19156	0.6	5.73	5	1930	<5	0.90	<1	7	74	78	2.18	1.94	10	1.59	2316	<1	0.88	17	570	32	<5	<20	92	0.13	<10	47	<10	5	6
12	S07-19157	0.4	5.50	5	1645	<5	1.03	<1	12	133	43	2.32	1.79	20	1.81	2404	<1	0.86	24	520	28	<5	<20	111	0.12	<10	49	<10	6	7
13	S07-19158	0.6	4.00	15	920	<5	1.15	<1	18	217	68	2.58	1.20	20	1.85	1730	<1	0.64	54	350	40	<5	<20	113	0.14	<10	69	<10	6	5
14	S07-19159	0.2	4.53	65	1405	<5	4.95	<1	33	677	8	3.74	1.84	<10	4.42	3100	<1	0.38	223	620	28	5	<20	417	0.09	<10	117	<10	7	9
15	S07-19160	0.4	6.10	30	1320	<5	4.68	<1	38	549	86	4.80	2.46	<10	5.57	2686	<1	0.35	200	950	32	5	<20	395	0.11	<10	166	<10	6	7
16	S07-19161	0.4	3.74	35	410	<5	6.30	<1	48	812	5	5.02	1.52	<10	6.98	4180	<1	0.33	433	580	26	10	<20	507	0.05	<10	135	<10	5	12
17	S07-19162	0.4	3.44	<5	1140	<5	0.74	<1	6	112	57	1.71	1.36	<10	1.09	995	2	0.21	21	240	22	<5	<20	68	0.09	<10	63	<10	7	2
18	S07-19163	0.2	5.83	5	2300	<5	0.76	<1	7	34	11	2.10	2.32	20	1.45	1894	<1	0.74	18	280	26	<5	<20	85	0.13	<10	33	<10	5	7
19	S07-19164	0.2	5.61	<5	2245	<5	0.79	<1	7	49	13	2.09	2.31	20	1.46	1879	<1	0.70	18	270	28	<5	<20	86	0.13	<10	33	<10	5	6
20	S07-19165	0.4	6.67	10	2260	<5	0.81	2	12	48	88	2.55	2.52	20	1.78	2787	<1	1.10	32	360	32	<5	<20	103	0.14	<10	38	<10	6	21
21	S07-19166	0.2	5.91	15	2365	<5	0.70	<1	6	35	12	2.06	2.34	20	1.57	2025	<1	0.83	20	270	34	<5	<20	92	0.12	<10	47	<10	6	7
22	S07-19167	0.2	6.26	5	2255	<5	1.14	<1	6	40	30	1.99	2.29	20	1.71	1784	<1	0.84	14	360	24	<5	<20	117	0.16	<10	87	<10	7	6
23	S07-19168	0.4	5.61	15	1565	<5	1.84	<1	21	136	246	3.73	2.04	20	2.51	3103	<1	0.81	56	650	38	<5	<20	192	0.16	<10	154	<10	8	10
24	S07-19169	0.4	5.58	20	1470	<5	1.29	<1	26	82	42	4.19	1.88	20	1.62	3013	<1	1.26	69	510	44	<5	<20	131	0.16	<10	93	<10	6	9
25	S07-19170	0.8	3.95	15	1190	<5	1.05	<1	25	65	102	2.90	1.58	20	1.28	2258	<1	0.67	65	440	46	<5	<20	98	0.14	<10	73	<10	4	7

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
26	S07-19171	0.6	4.61	15	1115	<5	0.81	<1	27	81	89	3.44	1.75	20	1.48	2525	<1	0.96	71	420	34	<5	<20	89	0.17	<10	84	<10	5	72
27	S07-19172	<0.2	0.13	<5	30	<5	>10	<1	<1	1	2	0.58	0.05	<10	>10	204	<1	0.04	3	210	2	<5	<20	61	<0.01	<10	3	<10	<1	14
28	S07-19173	0.2	3.32	15	575	<5	1.17	<1	16	181	27	2.30	1.21	10	1.39	1344	3	0.70	47	370	26	<5	<20	138	0.12	<10	83	<10	5	80
29	S07-19174	0.6	3.68	20	620	<5	2.04	<1	22	248	25	2.96	1.55	10	2.42	1767	<1	0.45	114	520	286	<5	<20	225	0.10	<10	87	<10	5	46
30	S07-19175	0.6	5.12	15	765	<5	1.65	<1	28	120	119	3.71	1.78	20	1.85	2429	<1	1.29	71	570	50	<5	<20	150	0.13	<10	103	<10	5	78
31	S07-19176	0.6	5.25	35	820	<5	0.91	<1	23	122	97	3.72	1.74	20	1.59	2240	<1	1.15	66	470	40	<5	<20	103	0.14	<10	88	<10	7	77
32	S07-19177	0.4	5.53	10	1375	<5	0.72	3	5	46	22	1.83	2.38	10	1.29	1008	<1	0.48	11	330	48	<5	<20	79	0.13	<10	23	<10	7	292
33	S07-19178	0.4	5.51	<5	1345	<5	0.61	<1	4	32	47	1.81	2.30	10	1.27	881	<1	0.72	9	320	28	<5	<20	75	0.14	<10	25	<10	6	44
34	S07-19179	0.6	5.83	10	1405	<5	0.53	<1	6	41	76	2.19	2.42	10	1.69	792	<1	0.77	13	320	36	<5	<20	69	0.15	<10	24	<10	7	34
35	S07-19180	0.2	4.62	35	680	<5	3.58	<1	35	570	2	3.92	2.01	10	6.39	2223	<1	0.28	282	460	24	5	<20	283	0.05	<10	94	<10	6	74
36	S07-19181	0.2	5.48	15	860	<5	2.73	<1	26	390	85	2.61	2.32	10	4.73	1500	<1	0.43	167	490	28	10	<20	211	0.09	<10	99	<10	7	66
37	S07-19182	0.2	4.82	30	810	<5	2.05	<1	22	360	7	2.43	2.14	20	4.59	1212	<1	0.37	214	450	22	<5	<20	170	0.08	<10	60	<10	8	44
38	S07-19183	6.6	3.99	150	425	<5	0.42	<1	7	41	54	3.42	2.99	<10	0.28	241	7	0.50	23	450	20	65	<20	100	0.31	<10	53	<10	10	51
39	S07-19184	<0.2	5.79	20	1270	<5	1.37	<1	12	187	13	2.04	2.59	20	2.90	715	1	0.37	72	330	24	<5	<20	121	0.09	<10	36	<10	8	31
40	S07-19185	0.2	6.33	5	1845	<5	0.52	<1	3	42	60	1.65	2.84	30	1.51	323	<1	0.46	11	300	28	<5	<20	63	0.12	<10	21	<10	7	17
41	S07-19186	0.2	5.55	15	1335	<5	1.37	<1	12	174	62	2.05	2.43	20	2.87	570	<1	0.29	68	310	26	<5	<20	110	0.10	<10	40	<10	7	32
42	S07-19187	<0.2	5.51	30	785	<5	3.37	<1	35	639	2	3.67	2.37	10	6.74	1380	<1	0.33	309	380	24	5	<20	239	0.05	<10	79	<10	7	59
43	S07-19188	<0.2	3.17	50	385	<5	4.23	<1	33	627	3	3.58	1.43	<10	6.55	1573	2	0.19	315	290	16	10	<20	373	0.03	<10	74	<10	4	54
44	S07-19189	<0.2	5.08	5	1340	<5	1.67	<1	7	86	46	2.11	2.36	20	1.82	1008	2	0.27	19	320	24	<5	<20	170	0.11	<10	35	<10	5	24
45	S07-19190	<0.2	5.72	30	1520	<5	2.25	<1	14	161	4	2.91	2.65	20	2.98	1936	2	0.14	100	500	36	<5	<20	216	0.12	<10	82	<10	10	45
46	S07-19191	0.2	3.34	15	820	<5	1.99	<1	6	149	3	1.72	1.61	<10	1.58	1077	3	0.06	39	260	62	<5	<20	231	0.06	<10	44	<10	6	19
47	S07-19192	0.8	5.70	15	1345	<5	1.66	<1	12	98	69	2.67	2.29	10	1.84	2207	<1	0.75	44	450	38	<5	<20	181	0.15	<10	79	<10	4	64
48	S07-19193	0.2	5.80	20	1210	<5	1.06	<1	37	71	67	3.52	1.95	20	1.78	2600	<1	1.15	47	560	36	<5	<20	124	0.15	<10	105	<10	5	75
49	S07-19194	0.2	4.86	20	1285	<5	1.73	<1	20	130	36	2.82	1.83	10	1.98	2161	<1	0.66	68	580	42	<5	<20	174	0.12	<10	147	<10	5	60
50	S07-19195	0.2	3.93	20	910	<5	0.80	<1	14	80	104	2.32	1.13	20	1.00	1527	1	1.21	44	390	34	<5	<20	93	0.12	<10	66	<10	4	49
51	S07-19196	0.4	4.38	10	1320	<5	1.03	<1	14	74	80	2.21	1.43	20	1.06	1708	<1	1.08	39	440	40	<5	<20	110	0.12	<10	64	<10	4	59
52	S07-19197	0.2	4.28	10	1285	<5	1.01	<1	14	69	87	2.10	1.39	20	1.03	1603	<1	1.10	39	420	32	<5	<20	108	0.12	<10	62	<10	4	57
53	S07-19198	0.4	4.68	15	1345	<5	1.60	<1	17	75	156	2.32	1.77	20	1.74	1310	<1	0.57	43	460	42	<5	<20	147	0.11	<10	90	<10	5	69
54	S07-19199	0.2	4.82	35	1135	<5	3.61	<1	32	446	85	4.31	2.02	<10	4.66	2415	<1	0.33	188	650	32	5	<20	307	0.09	<10	151	<10	5	84
55	S07-19200	0.2	4.37	30	1175	<5	1.67	<1	22	207	43	3.20	1.65	20	2.01	1830	<1	0.78	99	420	38	<5	<20	154	0.13	<10	88	<10	5	75
56	S07-19201	0.2	4.30	20	1250	<5	1.06	<1	18	111	80	2.85	1.58	20	1.22	1579	<1	0.76	54	460	44	<5	<20	105	0.14	<10	74	<10	5	55
57	S07-19202	0.4	5.08	40	1550	<5	1.64	<1	31	257	38	3.77	2.06	10	2.28	1936	<1	0.24	123	450	396	<5	<20	177	0.12	<10	107	<10	5	139
58	S07-19203	1.2	5.41	30	1880	<5	0.90	<1	29	182	82	3.97	2.01	30	1.33	2312	<1	1.13	65	460	42	<5	<20	108	0.19	<10	72	<10	6	69
59	S07-19204	3.8	5.98	20	2020	<5	1.12	<1	23	135	49	4.00	2.03	20	1.61	2313	<1	1.32	52	560	54	<5	<20	128	0.22	<10	141	<10	5	99
60	S07-19205	0.4	5.61	15	2020	<5	1.05	<1	18	171	156	3.51	2.08	20	1.77	2404	<1	1.16	35	580	34	<5	<20	127	0.19	<10	104	<10	5	99
61	S07-19206	<0.2	6.03	10	2035	<5	0.96	<1	14	102	162	3.20	2.14	10	1.81	2853	<1	1.30	26	450	42	<5	<20	126	0.18	<10	112	<10	5	79
62	S07-19207	0.2	0.08	<5	20	<5	>10	<1	<1	2	<1	0.53	0.04	<10	>10	189	<1	0.02	2	200	8	<5	<20	60	<0.01	<10	2	<10	<1	12
63	S07-19208	0.6	5.98	15	1660	<5	0.93	<1	19	181	131	3.91	2.06	20	1.87	2889	<1	1.27	42	650	46	<5	<20	120	0.21	<10	89	<10	7	80
64	S07-19209	0.4	4.39	20	1050	<5	1.14	<1	19	226	71	4.12	1.62	20	1.59	2442	<1	0.49	47	560	44	<5	<20	122	0.15	<10	78	<10	6	69
65	S07-19210	0.2	4.71	15	1225	<5	1.16	<1	19	295	74	3.91	1.50	20	1.61	2452	<1	0.83	44	520	52	<5	<20	124	0.17	<10	74	<10	5	89

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Z
66	S07-19211	<0.2	5.48	5	1555	<5	0.98	<1	3	220	12	1.96	1.51	<10	0.93	1913	<1	1.66	10	480	34	<5	<20	145	0.15	<10	44	<10	4	6
67	S07-19212	<0.2	5.91	<5	1665	<5	0.84	<1	3	183	7	2.02	1.60	10	1.00	2187	<1	2.08	9	560	50	<5	<20	143	0.17	<10	47	<10	5	3
68	S07-19213	4.7	4.45	140	340	<5	0.50	1	11	37	595	5.01	2.45	10	1.76	392	8	0.21	26	550	116	45	<20	76	0.31	<10	55	<10	11	61
69	S07-19214	<0.2	6.41	5	2005	<5	0.77	<1	7	143	49	2.37	1.95	20	1.30	2638	<1	1.70	17	540	36	<5	<20	116	0.20	<10	46	<10	7	10
70	S07-19215	<0.2	6.38	10	1880	<5	0.66	<1	8	201	18	2.16	2.08	10	1.18	2237	<1	1.56	16	590	36	<5	<20	108	0.19	<10	37	<10	7	6
71	S07-19216	0.4	6.17	<5	1980	<5	1.34	<1	11	311	49	2.97	2.57	20	1.61	2420	<1	0.68	23	700	36	5	<20	141	0.16	<10	56	<10	6	6
72	S07-19217	1.0	5.45	25	1140	<5	3.13	<1	34	542	48	5.17	2.52	10	4.11	3037	<1	0.18	215	610	48	10	<20	236	0.12	<10	117	<10	6	11
73	S07-19218	0.8	5.08	20	845	<5	3.50	<1	33	558	85	5.15	2.41	<10	4.86	2769	<1	0.20	221	670	36	10	<20	250	0.11	<10	161	<10	6	10
74	S07-19219	0.4	5.44	30	935	<5	2.36	<1	39	346	7	4.94	2.51	20	4.56	2525	<1	0.20	246	580	34	10	<20	188	0.15	<10	193	<10	8	10
75	S07-19220	1.0	3.77	20	575	<5	3.87	<1	39	589	67	4.52	1.58	<10	4.55	2998	<1	0.28	310	470	32	20	<20	258	0.08	<10	105	<10	5	11
76	S07-19221	0.8	4.26	15	900	<5	0.84	<1	24	278	118	4.26	1.20	20	1.91	2009	<1	0.65	71	440	50	5	<20	78	0.13	<10	53	<10	5	6
77	S07-19222	0.6	3.68	10	935	<5	1.38	<1	20	236	67	3.51	1.22	10	1.18	2367	<1	0.83	59	390	44	<5	<20	121	0.10	<10	64	<10	5	8
78	S07-19223	0.8	4.48	10	1270	<5	1.05	<1	22	258	105	3.77	1.81	20	1.31	2412	<1	0.50	66	670	40	<5	<20	97	0.12	<10	73	<10	7	5
79	S07-19224	1.4	4.30	10	980	<5	1.70	<1	27	512	104	4.45	1.84	20	2.31	2047	<1	0.26	89	480	334	10	<20	138	0.10	<10	84	<10	5	7
80	S07-19225	2.4	3.27	10	350	<5	5.32	<1	37	475	645	5.10	1.40	<10	5.89	2540	<1	0.19	182	800	20	10	<20	349	0.04	<10	139	<10	4	8
81	S07-19226	0.8	3.41	10	535	<5	3.75	<1	27	473	103	4.66	1.48	<10	4.21	2355	<1	0.22	119	670	40	5	<20	265	0.05	<10	93	<10	4	6
82	S07-19227	1.8	4.55	15	1135	<5	1.13	<1	27	370	211	4.24	1.72	20	1.65	1846	<1	0.32	80	610	52	5	<20	89	0.12	<10	56	<10	8	5
83	S07-19228	1.0	4.12	10	1145	<5	1.11	<1	17	224	157	3.69	1.64	20	1.43	2073	<1	0.49	56	390	32	<5	<20	98	0.11	<10	51	<10	7	4
84	S07-19229	0.8	3.73	10	900	<5	1.09	<1	20	224	79	3.67	1.27	20	1.15	2118	<1	0.71	59	440	48	5	<20	109	0.09	<10	43	<10	6	8
85	S07-19230	0.4	6.16	<5	2305	<5	1.04	<1	9	75	37	2.56	2.68	20	1.44	1617	<1	0.65	25	340	34	<5	<20	114	0.12	<10	36	<10	7	6
86	S07-19231	0.6	5.36	10	1575	<5	0.84	<1	19	156	76	3.86	2.07	20	1.58	2784	<1	0.83	54	440	48	<5	<20	90	0.14	<10	78	<10	8	9
87	S07-19232	0.8	5.01	5	1390	<5	0.80	<1	22	174	82	4.05	1.89	20	1.65	2850	<1	0.95	60	490	50	<5	<20	91	0.14	<10	77	<10	8	9
88	S07-19233	0.6	4.16	10	1300	<5	1.66	<1	20	381	133	3.77	1.81	20	2.12	2269	<1	0.32	68	490	46	5	<20	159	0.10	<10	80	<10	6	9
89	S07-19234	0.6	5.83	5	1700	<5	0.79	<1	20	258	164	4.70	2.11	20	2.04	3124	<1	1.23	44	630	42	<5	<20	99	0.17	<10	88	<10	7	7
90	S07-19235	0.4	5.99	<5	2040	<5	0.82	<1	7	171	38	2.72	2.00	10	1.45	2495	<1	1.68	14	570	34	<5	<20	117	0.14	<10	52	<10	5	6
91	S07-19236	<0.2	6.67	<5	2130	<5	0.66	<1	5	78	16	2.29	2.04	10	1.24	2461	<1	2.23	10	700	32	<5	<20	132	0.13	<10	48	<10	6	5
92	S07-19237	0.4	5.90	<5	1805	<5	0.61	<1	9	60	53	2.40	1.79	10	1.26	2491	<1	1.80	16	540	34	<5	<20	103	0.14	<10	40	<10	6	6
93	S07-19238	0.6	5.72	<5	1755	<5	0.90	<1	10	68	52	2.66	2.01	10	1.51	2557	<1	1.25	19	610	32	<5	<20	108	0.13	<10	46	<10	5	7
94	S07-19239	0.8	5.12	5	1390	<5	0.71	<1	19	124	106	3.54	2.07	20	1.62	2495	<1	0.83	47	510	44	<5	<20	86	0.14	<10	64	<10	7	7
95	S07-19240	<0.2	0.06	<5	15	<5	>10	<1	<1	3	2	0.53	0.03	<10	>10	198	<1	0.01	2	310	6	<5	<20	59	<0.01	<10	3	<10	<1	1
96	S07-19241	0.6	5.15	30	1180	<5	3.41	<1	36	348	28	4.69	2.32	10	4.68	2910	<1	0.27	213	610	38	5	<20	284	0.13	<10	150	<10	8	10
97	S07-19242	0.8	4.47	15	1065	<5	1.01	<1	22	116	80	3.64	1.69	20	1.68	2092	<1	0.18	65	460	44	<5	<20	88	0.12	<10	90	<10	6	7
98	S07-19243	1.0	4.42	15	1265	<5	1.31	<1	26	89	82	3.74	1.85	20	1.41	2630	<1	0.30	64	470	40	<5	<20	119	0.11	<10	90	<10	6	8
99	S07-19244	0.8	5.52	20	1395	<5	1.62	<1	28	126	64	4.57	2.29	20	1.82	2990	<1	0.49	71	650	54	<5	<20	157	0.13	<10	96	<10	7	8
100	S07-19245	0.8	4.45	15	920	<5	1.20	<1	19	103	118	4.02	1.62	20	1.44	1875	<1	0.76	52	520	36	<5	<20	121	0.12	<10	104	<10	6	8
101	S07-19246	0.2	5.07	20	635	<5	6.03	<1	41	385	75	6.47	2.33	<10	6.04	3432	<1	0.32	145	1360	22	5	<20	523	0.06	<10	181	<10	6	7
102	S07-19247	0.4	7.61	<5	2175	<5	1.08	<1	8	48	34	2.23	2.82	20	2.04	2370	<1	1.58	19	480	34	<5	<20	160	0.18	<10	111	<10	7	6
103	S07-19248	0.4	6.15	<5	2140	<5	0.67	<1	7	55	30	1.95	2.47	20	1.58	2347	<1	1.14	17	340	26	<5	<20	108	0.13	<10	70	<10	7	7
104	S07-19249	0.2	5.68	<5	1925	<5	0.70	<1	4	67	15	1.85	2.29	10	1.47	2476	<1	0.91	14	310	30	<5	<20	106	0.11	<10	77	<10	6	8
105	S07-19250	0.4	6.58	<5	2100	<5	0.87	<1	6	53	22	1.81	2.74	20	1.61	2660	<1	0.86	13	320	42	<5	<20	118	0.13	<10	112	<10	6	7

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Z
106	S07-19251	0.8	5.80	90	365	<5	0.26	<1	7	24	33	3.37	4.60	10	0.31	170	3	0.10	15	510	20	45	<20	54	0.34	<10	68	<10	11	4
107	S07-19252	1.0	4.86	5	1085	<5	2.24	<1	21	195	182	3.95	2.04	10	2.69	2517	<1	0.27	60	670	32	<5	<20	205	0.11	<10	134	<10	7	8
108	S07-19253	0.6	5.99	20	1050	<5	2.06	<1	35	199	58	5.71	2.35	20	2.70	2857	<1	0.93	100	770	42	5	<20	195	0.13	<10	117	<10	7	10
109	S07-19254	0.8	6.24	15	1250	<5	1.72	<1	29	138	143	5.19	2.49	30	2.21	2679	<1	1.09	80	680	42	<5	<20	161	0.14	<10	115	<10	7	11
110	S07-19255	1.0	4.45	20	950	<5	2.24	<1	29	268	77	4.00	1.83	20	2.15	2582	<1	0.53	109	510	122	<5	<20	180	0.11	<10	100	<10	6	7
111	S07-19256	0.6	5.29	<5	1555	<5	1.90	<1	14	204	41	3.07	2.51	10	2.62	2116	<1	0.58	56	570	32	<5	<20	174	0.12	<10	79	<10	8	6
112	S07-19257	0.4	6.25	<5	2130	<5	0.95	<1	5	73	13	1.92	2.67	20	1.44	1585	<1	0.39	16	330	32	<5	<20	89	0.14	<10	25	<10	7	7
113	S07-19258	0.4	6.30	<5	1730	<5	0.96	<1	16	88	81	3.42	2.34	20	1.68	2568	<1	1.17	42	370	36	<5	<20	100	0.14	<10	50	<10	8	8
114	S07-19259	0.8	3.66	5	505	<5	1.08	<1	16	106	201	2.90	0.92	20	1.39	1913	<1	1.55	45	410	42	<5	<20	115	0.09	<10	43	<10	5	6
115	S07-19260	0.4	4.98	5	1090	<5	2.02	<1	10	149	41	2.37	1.98	20	2.17	2337	<1	0.82	50	450	26	<5	<20	168	0.10	<10	65	<10	9	5
116	S07-19261	0.4	5.51	<5	1305	<5	0.69	<1	6	50	9	1.83	2.31	20	1.43	1779	<1	0.80	15	280	68	<5	<20	82	0.11	<10	26	<10	7	4
117	S07-19262	0.4	4.96	<5	1100	<5	0.74	<1	5	58	4	1.78	2.12	20	1.40	1431	<1	0.49	15	220	28	<5	<20	75	0.10	<10	23	<10	5	4
118	S07-19263	<0.2	4.13	25	695	<5	3.11	<1	23	368	4	3.47	1.99	10	4.29	3232	<1	0.19	209	370	28	5	<20	251	0.07	<10	69	<10	6	13
119	S07-19264	0.4	4.02	25	630	<5	3.34	2	25	476	5	3.98	1.89	10	4.94	3486	<1	0.21	252	440	72	10	<20	266	0.07	<10	67	<10	6	28
120	S07-19265	0.2	5.24	20	835	<5	2.36	<1	24	382	1	3.10	2.55	<10	3.88	2217	<1	0.16	230	400	30	5	<20	178	0.11	<10	73	<10	9	9
121	S07-19266	<0.2	5.18	<5	955	<5	0.88	<1	6	134	2	2.06	2.55	10	2.21	1127	<1	0.11	29	260	24	<5	<20	95	0.11	<10	49	<10	8	3
122	S07-19267	0.4	5.69	15	965	<5	2.00	<1	13	261	3	3.14	2.71	10	3.47	2388	<1	0.16	95	260	20	<5	<20	161	0.11	<10	64	<10	9	6
123	S07-19268	0.4	4.06	40	355	<5	5.59	<1	43	654	3	4.76	1.90	<10	7.35	3008	<1	0.29	438	490	18	10	<20	415	0.04	<10	103	<10	7	10
124	S07-19269	<0.2	5.99	<5	1000	<5	0.28	<1	6	52	2	2.52	3.04	10	3.62	681	<1	0.24	28	410	30	<5	<20	43	0.13	<10	78	<10	7	4
125	S07-19270	<0.2	5.81	<5	945	<5	0.61	<1	11	126	2	2.75	2.76	10	3.31	1089	<1	0.18	56	380	36	<5	<20	73	0.13	<10	73	<10	9	3
126	S07-19271	<0.2	6.40	10	1030	<5	1.48	<1	15	190	3	2.82	2.46	10	3.79	1401	<1	0.26	101	460	36	<5	<20	110	0.14	<10	75	<10	10	4
127	S07-19272	<0.2	0.09	<5	20	<5	>10	<1	<1	3	2	0.54	0.04	<10	>10	198	<1	0.03	3	270	12	<5	<20	57	<0.01	<10	3	<10	<1	1
128	S07-19273	0.2	3.93	35	240	<5	5.79	<1	48	800	12	5.04	1.74	<10	7.85	3274	<1	0.38	483	570	36	15	<20	369	0.04	<10	105	<10	5	12
129	S07-19274	0.2	4.90	5	775	<5	1.88	<1	15	251	3	2.87	2.40	<10	3.79	1665	<1	0.23	111	440	24	<5	<20	149	0.10	<10	74	<10	8	5
130	S07-19275	0.4	5.71	<5	1030	<5	0.41	<1	5	66	76	1.77	2.62	10	1.41	704	<1	0.28	11	290	32	<5	<20	42	0.14	<10	24	<10	5	3
131	S07-19276	1.0	6.25	<5	1105	<5	0.41	<1	7	82	94	2.49	2.97	10	1.91	940	<1	0.24	18	290	36	<5	<20	47	0.15	<10	29	<10	5	4
132	S07-19277	0.4	6.07	10	995	<5	1.48	<1	15	156	13	2.81	2.89	10	2.67	1163	<1	0.23	56	410	38	<5	<20	120	0.13	<10	45	<10	5	5
133	S07-19278	0.4	5.40	30	550	<5	5.33	<1	37	489	23	5.64	2.55	<10	6.29	2252	<1	0.34	224	660	32	5	<20	354	0.07	<10	129	<10	6	7
134	S07-19279	0.2	7.11	20	915	<5	4.27	<1	20	316	4	4.42	2.28	10	4.27	2521	<1	0.38	126	430	44	<5	<20	315	0.13	<10	83	<10	9	5
135	S07-19280	0.6	4.74	25	465	<5	6.34	<1	32	463	6	5.15	2.40	<10	5.97	2408	<1	0.27	195	630	36	10	<20	428	0.07	<10	135	<10	6	6
136	S07-19281	0.4	6.12	30	360	<5	5.64	<1	38	468	58	6.36	2.15	<10	5.93	1467	<1	0.68	259	940	36	5	<20	319	0.10	<10	176	<10	6	6
137	S07-19282	6.6	4.19	160	365	<5	0.44	<1	7	44	56	3.55	2.98	<10	0.29	251	6	0.50	23	480	16	70	<20	101	0.29	<10	57	<10	11	5
138	S07-19283	0.8	5.08	10	195	<5	4.85	<1	29	461	11	4.73	1.89	<10	6.71	1808	<1	0.45	278	540	26	5	<20	224	0.07	<10	85	<10	7	6
139	S07-19284	0.2	3.56	40	105	<5	6.41	<1	57	740	6	5.39	1.32	<10	9.99	1824	<1	0.27	584	550	22	10	<20	271	0.02	<10	107	<10	5	5
140	S07-19285	1.0	3.91	35	80	<5	6.34	<1	46	677	7	5.10	1.16	<10	8.78	1810	<1	0.22	409	640	446	10	<20	249	0.03	<10	124	<10	6	5
141	S07-19286	0.4	4.36	20	210	<5	5.94	<1	34	551	12	5.57	2.11	<10	8.23	2621	<1	0.25	222	780	24	5	<20	277	0.04	<10	144	<10	5	9
142	S07-19287	1.0	5.64	35	415	<5	3.36	<1	24	505	183	3.15	2.15	10	3.55	1648	<1	0.71	245	530	44	10	<20	227	0.09	<10	56	<10	9	5
143	S07-19288	0.6	4.53	40	200	<5	6.07	<1	48	767	65	5.03	1.92	<10	7.78	1987	<1	0.29	527	540	28	15	<20	233	0.05	<10	97	<10	5	5
144	S07-19289	0.2	3.57	25	130	<5	6.99	<1	43	503	5	5.23	1.69	<10	9.28	2293	<1	0.20	392	640	24	5	<20	276	0.04	<10	122	<10	6	5
145	S07-19290	0.4	5.81	15	1095	<5	2.04	<1	16	247	35	2.73	2.96	10	2.96	1380	3	0.19	138	400	32	5	<20	129	0.13	<10	41	<10	9	5

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Z
146	S07-19291	0.4	4.54	35	570	<5	1.70	<1	32	492	99	3.80	2.17	10	3.78	1155	<1	0.13	278	460	28	10	<20	76	0.09	<10	72	<10	5	6
147	S07-19292	0.4	3.82	40	190	<5	5.14	<1	43	724	26	4.90	1.90	<10	6.61	1790	<1	0.23	388	530	26	10	<20	245	0.05	<10	116	<10	4	8
148	S07-19293	0.8	4.46	35	180	<5	4.64	<1	44	552	70	5.65	2.07	<10	7.07	1729	<1	0.28	307	680	28	10	<20	204	0.08	<10	137	<10	4	6
149	S07-19294	<0.2	4.40	40	235	<5	5.23	<1	44	616	11	4.69	2.07	<10	6.79	1996	<1	0.28	381	570	26	10	<20	231	0.05	<10	99	<10	5	7
150	S07-19295	0.4	4.58	20	260	<5	3.75	<1	31	438	14	4.19	2.13	<10	6.53	1541	<1	0.24	286	500	32	10	<20	180	0.07	<10	74	<10	6	7
151	S07-19296	6.2	3.68	30	135	10	5.10	<1	37	514	20	4.66	1.70	<10	7.13	1573	<1	0.26	296	600	1180	10	<20	251	0.05	<10	112	<10	5	6
152	S07-19297	0.4	5.85	55	470	<5	4.11	<1	35	502	61	4.86	2.20	<10	5.35	1344	<1	0.37	308	700	40	10	<20	173	0.11	<10	88	<10	8	5
153	S07-19298	0.6	4.72	15	205	<5	4.27	<1	29	498	46	5.24	2.29	<10	7.80	1676	<1	0.39	150	810	28	10	<20	258	0.06	<10	157	<10	4	5
154	S07-19299	0.6	5.66	15	495	<5	4.06	<1	12	140	107	3.23	2.04	10	2.23	1336	7	0.17	58	490	32	<5	<20	188	0.12	<10	85	<10	9	7
155	S07-19300	0.8	6.00	20	250	<5	2.77	3	16	139	70	5.78	2.24	20	1.41	866	44	0.15	96	900	38	<5	<20	126	0.11	<10	334	<10	7	26
156	S07-19301	<0.2	0.04	<5	20	<5	>10	<1	<1	2	1	0.04	0.01	<10	1.73	25	<1	0.01	19	60	12	<5	<20	5824	<0.01	<10	4	<10	<1	
157	S07-19302	1.2	5.40	15	195	<5	4.57	3	14	134	150	6.83	2.21	20	2.00	1226	37	0.14	74	970	64	5	<20	198	0.10	<10	233	<10	7	25
158	S07-19303	1.2	5.34	15	200	<5	3.73	2	13	188	134	5.55	2.05	20	1.85	924	36	0.13	64	900	66	10	<20	188	0.11	<10	242	<10	8	18
159	S07-19304	1.0	4.95	20	155	<5	3.76	7	15	234	81	5.65	2.27	20	1.64	1020	53	0.10	98	990	86	5	<20	167	0.11	<10	307	<10	7	53
160	S07-19305	0.6	4.53	15	180	<5	3.19	4	12	158	36	3.67	2.12	20	1.55	925	33	0.08	95	700	38	<5	<20	149	0.12	<10	287	<10	6	29
161	S07-19306	0.6	4.98	15	255	<5	3.61	4	15	229	47	4.45	2.11	20	1.61	986	31	0.09	87	970	52	10	<20	161	0.13	<10	353	<10	7	33
162	S07-19307	1.2	6.25	15	150	<5	2.38	2	14	271	44	5.98	2.29	20	1.18	747	35	0.16	66	890	74	10	<20	116	0.13	<10	195	<10	8	19
163	S07-19308	0.8	6.87	15	865	<5	2.04	<1	12	174	61	2.83	2.51	20	1.29	941	7	0.25	36	410	50	<5	<20	110	0.16	<10	82	<10	9	4
164	S07-19309	0.6	6.08	10	805	<5	1.42	<1	10	172	65	1.97	2.82	20	1.04	915	1	0.21	22	350	60	<5	<20	89	0.14	<10	55	<10	8	6
165	S07-19310	0.6	4.75	5	570	<5	2.52	2	7	194	43	1.99	2.22	20	1.17	1616	1	0.15	22	740	172	<5	<20	145	0.11	<10	46	<10	10	16
166	S07-19311	0.6	4.80	10	575	<5	2.74	2	10	202	46	2.25	2.28	20	1.20	1768	<1	0.16	25	1010	204	<5	<20	171	0.10	<10	47	<10	10	18
167	S07-19312	0.4	4.76	20	395	<5	4.44	<1	25	401	40	3.71	2.27	20	3.68	2296	<1	0.23	127	790	50	5	<20	209	0.10	<10	122	<10	7	9
168	S07-19313	0.4	5.45	35	215	<5	4.01	<1	46	615	43	6.27	2.38	<10	6.66	2105	2	0.30	262	790	54	10	<20	195	0.11	<10	169	<10	4	17
169	S07-19314	0.6	5.68	20	515	<5	4.65	<1	34	556	110	5.30	2.71	<10	4.28	1688	4	0.36	144	750	74	10	<20	255	0.10	<10	194	<10	6	11
170	S07-19315	0.4	4.77	20	430	<5	3.51	<1	25	561	73	4.55	2.50	<10	4.59	1280	4	0.34	136	670	56	5	<20	175	0.09	<10	188	<10	4	10
171	S07-19316	0.6	4.66	45	235	<5	5.11	<1	46	649	61	5.32	2.02	<10	5.21	1957	<1	0.52	304	750	44	10	<20	223	0.07	<10	138	<10	5	7
172	S07-19317	0.8	4.75	15	405	<5	3.42	<1	22	311	109	4.11	1.97	20	2.11	1080	9	0.40	70	620	56	5	<20	156	0.10	<10	151	<10	5	4
173	S07-19318	4.8	4.12	190	265	<5	0.51	1	10	35	569	4.97	2.54	10	1.91	361	6	0.22	22	500	106	45	<20	80	0.25	<10	59	<10	12	56
174	S07-19319	0.6	4.78	40	305	<5	2.21	<1	37	481	78	5.79	2.12	10	4.25	1351	22	0.34	194	610	46	10	<20	110	0.10	<10	158	<10	3	8
175	S07-19320	0.6	6.00	30	580	<5	3.19	<1	32	607	43	4.42	2.99	20	4.48	1645	8	0.29	205	530	58	10	<20	182	0.11	<10	126	<10	8	10
176	S07-19321	1.0	3.94	65	190	<5	4.92	11	42	828	35	5.03	1.98	<10	6.16	2516	1	0.24	302	540	102	10	<20	422	0.06	<10	132	<10	4	102
177	S07-19322	0.8	4.59	40	335	<5	2.37	<1	26	338	30	4.46	2.25	<10	4.52	966	5	0.18	150	620	30	<5	<20	129	0.10	<10	147	<10	5	10
178	S07-19323	0.8	6.23	40	265	<5	2.50	<1	51	702	67	6.83	2.27	10	5.45	1735	16	0.25	293	790	32	10	<20	103	0.12	<10	160	<10	4	14
179	S07-19324	0.4	4.19	20	265	<5	1.53	<1	26	282	105	4.50	1.95	10	2.34	792	18	0.12	103	440	26	<5	<20	99	0.10	<10	140	<10	5	5
180	S07-19325	0.6	5.84	20	585	<5	5.85	<1	23	222	116	3.99	2.54	20	2.67	3697	<1	0.64	59	900	38	<5	<20	331	0.12	<10	262	<10	9	7
181	S07-19326	0.4	4.48	25	230	<5	4.54	<1	34	540	38	5.07	2.19	<10	6.39	3638	<1	0.31	183	660	24	5	<20	204	0.08	<10	188	<10	5	7
182	S07-19327	0.2	4.72	25	110	<5	4.30	<1	53	739	67	5.93	1.73	<10	7.47	2088	<1	0.29	385	830	20	10	<20	135	0.06	<10	141	<10	5	8
183	S07-19328	0.8	3.99	50	200	<5	5.84	<1	39	452	74	4.95	1.84	<10	6.49	1521	<1	0.24	252	680	90	20	<20	254	0.06	<10	130	<10	6	5
184	S07-19329	0.8	3.77	45	225	<5	6.05	<1	38	517	32	4.93	1.82	<10	5.85	1708	<1	0.21	219	590	22	10	<20	384	0.05	<10	133	<10	5	5
185	S07-19330	0.6	4.64	20	160	<5	5.47	<1	28	300	56	5.24	2.00	<10	6.04	1131	<1	0.39	116	830	20	10	<20	228	0.09	<10	164	<10	6	4

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Z
186	S07-19331	0.6	4.79	15	90	<5	5.45	<1	37	465	83	5.81	1.65	<10	6.49	1244	<1	0.53	198	820	20	10	<20	213	0.11	<10	162	<10	6	5
187	S07-19332	0.6	4.65	25	165	<5	3.23	<1	22	342	147	4.49	1.66	20	2.73	1090	<1	0.51	116	460	26	<5	<20	230	0.10	<10	125	<10	7	5
188	S07-19333	0.8	5.19	35	200	<5	4.63	<1	43	644	50	4.96	1.81	<10	5.26	2063	<1	0.78	301	530	24	10	<20	222	0.08	<10	169	<10	5	7
189	S07-19334	0.2	4.77	20	170	<5	3.91	<1	42	609	53	4.75	1.64	<10	5.43	1947	<1	0.72	290	570	18	5	<20	201	0.08	<10	158	<10	5	7
190	S07-19335	0.4	6.18	25	350	<5	2.09	<1	23	221	131	4.08	1.96	20	1.51	1005	2	1.76	54	540	38	<5	<20	200	0.15	<10	105	<10	10	5
191	S07-19336	0.4	4.27	30	265	<5	3.46	<1	38	607	52	4.63	1.72	10	5.05	2209	1	0.38	293	550	18	10	<20	156	0.07	<10	104	<10	5	8
192	S07-19337	0.2	5.21	40	270	<5	3.20	<1	40	626	38	5.33	1.94	<10	6.47	2151	1	0.51	293	810	24	10	<20	192	0.07	<10	150	<10	4	8
193	S07-19338	0.8	5.55	20	430	<5	3.64	<1	30	489	68	4.33	2.00	10	4.50	1496	<1	0.59	233	520	22	5	<20	163	0.07	<10	83	<10	7	6
194	S07-19339	0.6	4.19	25	200	<5	3.63	<1	22	359	5	4.39	1.01	10	4.52	1587	<1	0.72	130	490	16	5	<20	204	0.07	<10	75	<10	7	4
195	S07-19340	0.4	4.29	15	100	<5	2.51	<1	38	548	56	5.17	1.26	<10	5.53	1408	<1	0.55	266	650	14	10	<20	94	0.09	<10	120	<10	5	6
196	S07-19341	0.6	4.75	20	160	<5	3.33	<1	47	681	34	5.84	1.27	<10	6.74	2249	<1	0.63	319	700	18	10	<20	115	0.08	<10	135	<10	4	10
197	S07-19342	<0.2	0.05	<5	15	<5	>10	<1	<1	3	1	0.54	0.03	<10	>10	185	<1	0.01	3	180	<2	<5	<20	54	<0.01	<10	3	<10	<1	1
198	S07-19343	0.4	4.18	40	150	<5	4.13	<1	40	635	59	5.36	1.27	<10	5.51	2159	<1	0.56	264	600	18	10	<20	153	0.11	<10	113	<10	5	8
199	S07-19344	0.6	4.35	20	65	<5	5.64	<1	47	692	40	5.43	1.22	<10	7.82	1567	<1	0.39	326	660	14	10	<20	159	0.06	<10	139	<10	5	7
200	S07-19345	0.2	4.06	30	125	<5	5.64	<1	31	408	24	4.81	1.74	<10	5.61	1639	<1	0.25	190	760	16	5	<20	252	0.07	<10	147	<10	5	6
201	S07-19346	0.8	6.66	15	655	<5	3.45	<1	24	256	137	4.22	3.15	20	3.25	1734	<1	0.37	77	600	38	<5	<20	245	0.15	<10	394	<10	8	8
202	S07-19347	0.6	5.08	35	370	<5	3.94	<1	24	377	77	4.25	2.23	20	3.45	2475	<1	0.21	126	620	46	5	<20	234	0.09	<10	89	<10	8	7
203	S07-19348	0.6	4.11	25	165	<5	5.41	<1	34	472	52	5.43	1.54	<10	5.66	2064	3	0.27	181	890	32	5	<20	263	0.06	<10	118	<10	6	6
204	S07-19349	0.8	5.18	40	400	<5	2.61	1	22	279	70	3.99	1.87	20	2.87	1387	1	0.20	88	570	80	<5	<20	185	0.10	<10	110	<10	8	14
205	S07-19350	0.4	3.91	55	145	<5	2.39	<1	33	633	33	4.37	1.76	<10	4.30	1817	9	0.19	220	460	22	10	<20	152	0.07	<10	104	<10	4	8
206	S07-19351	0.4	5.05	45	515	<5	5.44	<1	30	526	52	4.30	2.56	10	4.72	2094	<1	0.30	196	510	40	<5	<20	349	0.06	<10	131	<10	8	8
207	S07-19352	0.2	7.08	50	730	<5	6.03	<1	29	392	45	4.54	3.09	10	4.60	2300	14	0.34	185	650	50	<5	<20	315	0.10	<10	146	<10	8	9
208	S07-19353	1.2	5.55	15	295	<5	2.00	1	14	327	178	4.44	2.60	20	1.27	727	28	0.15	67	740	42	<5	<20	142	0.09	<10	192	<10	6	10
209	S07-19354	1.0	5.69	90	320	<5	0.27	<1	7	24	31	3.51	4.63	10	0.33	163	3	0.11	14	470	18	40	<20	50	0.34	<10	66	<10	11	4
210	S07-19355	1.0	4.64	20	195	<5	3.90	2	14	275	43	5.20	2.06	20	2.19	1558	24	0.11	73	950	54	5	<20	257	0.08	<10	151	<10	9	15
211	S07-19356	1.9	4.93	25	255	<5	4.22	<1	18	304	62	4.66	2.64	20	2.86	1123	23	0.19	83	730	42	10	<20	231	0.08	<10	219	<10	8	8
212	S07-19357	1.4	4.72	10	250	<5	3.53	1	12	288	48	4.38	2.56	20	2.43	868	20	0.15	65	790	40	5	<20	190	0.09	<10	197	<10	9	13
213	S07-19358	2.2	3.55	15	165	<5	2.64	<1	11	414	38	4.41	1.59	20	1.39	700	20	0.06	54	600	234	10	<20	126	0.08	<10	127	<10	7	9
214	S07-19359	1.8	4.91	20	175	<5	2.92	1	16	301	62	4.95	2.24	20	1.74	857	27	0.12	71	790	60	10	<20	157	0.11	<10	199	<10	9	14
215	S07-19360	0.6	5.96	15	265	<5	4.34	<1	14	238	68	3.93	3.13	20	2.52	1028	8	0.39	43	710	44	<5	<20	264	0.10	<10	133	<10	12	6
216	S07-19361	0.8	2.41	5	150	<5	1.52	<1	8	450	31	3.01	1.12	<10	0.76	522	15	0.04	39	820	32	5	<20	118	0.05	<10	108	<10	6	8
217	S07-19362	1.8	5.64	10	265	<5	3.09	2	15	257	40	4.73	2.65	20	1.64	995	25	0.13	61	1100	54	10	<20	200	0.10	<10	235	<10	9	17
218	S07-19363	1.4	4.63	5	275	<5	2.34	<1	6	170	19	3.01	2.17	20	1.25	639	12	0.09	27	490	36	<5	<20	133	0.09	<10	98	<10	9	5
219	S07-19364	1.2	6.68	10	255	<5	2.87	2	13	247	80	4.50	2.47	20	1.48	869	16	0.17	35	1020	44	5	<20	150	0.12	<10	136	<10	9	13
220	S07-19365	0.4	7.04	5	870	<5	4.92	<1	8	144	83	3.59	2.49	20	2.13	1457	5	0.31	10	1160	36	<5	<20	254	0.13	<10	70	<10	10	7
221	S07-19366	1.0	8.10	5	225	<5	3.24	<1	10	77	129	3.87	2.33	20	1.64	707	4	0.31	10	740	50	<5	<20	145	0.14	<10	90	<10	9	6
222	S07-19367	1.4	6.35	10	280	<5	2.23	1	12	211	79	4.03	3.07	20	1.31	585	16	0.18	39	740	46	<5	<20	134	0.12	<10	164	<10	10	12
223	S07-19368	0.6	7.14	5	395	<5	2.75	<1	10	106	33	2.99	2.71	20	1.44	572	2	0.26	9	600	40	<5	<20	135	0.12	<10	82	<10	8	6
224	S07-19369	0.2	5.76	15	270	<5	2.65	2	15	232	48	4.74	2.82	20	1.41	752	26	0.15	60	1110	44	5	<20	138	0.10	<10	227	<10	8	21
225	S07-19370	1.2	5.53	10	315	<5	2.73	2	16	252	68	4.85	2.64	20	1.35	807	29	0.12	71	1170	44	5	<20	132	0.10	<10	250	<10	7	20

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Z
226	S07-19371	0.6	5.94	10	255	<5	2.90	2	15	226	52	4.63	2.78	20	1.63	789	23	0.15	51	1030	42	<5	<20	155	0.11	<10	233	<10	9	17
227	S07-19372	<0.2	0.05	<5	30	<5	>10	<1	<1	2	<1	0.03	<0.01	<10	1.98	25	<1	<0.01	23	40	<2	<5	<20	6011	<0.01	<10	3	<10	<1	
228	S07-19373	0.6	6.47	15	180	<5	2.66	1	14	181	53	4.32	2.53	20	1.47	669	15	0.19	37	780	46	<5	<20	142	0.10	<10	202	<10	6	11
229	S07-19374	0.6	5.99	15	320	<5	3.29	1	13	175	80	3.65	2.48	20	1.64	787	13	0.53	30	1110	38	<5	<20	171	0.11	<10	230	<10	7	10
230	S07-19375	0.6	7.15	10	960	<5	5.61	2	13	144	120	3.67	2.19	10	2.17	1473	4	0.69	21	990	48	<5	<20	249	0.14	<10	167	<10	7	16
231	S07-19376	0.6	5.56	5	890	<5	4.82	1	10	143	138	3.16	2.13	10	2.28	1232	3	0.72	17	780	36	<5	<20	260	0.11	<10	159	<10	7	13
232	S07-19377	0.4	4.61	15	240	<5	2.51	2	14	262	43	4.30	2.15	20	1.12	796	24	0.28	45	1950	30	<5	<20	154	0.08	<10	168	<10	8	18
233	S07-19378	4.0	6.70	20	255	<5	2.49	3	15	222	38	3.45	2.00	20	1.46	698	12	0.59	51	1350	40	<5	<20	158	0.15	<10	183	<10	8	24
234	S07-19379	0.6	5.57	20	445	<5	1.93	<1	7	295	22	2.33	2.61	20	1.11	589	7	0.55	19	600	26	<5	<20	130	0.11	<10	103	<10	6	10
235	S07-19380	0.6	6.69	15	305	<5	3.17	<1	11	172	74	3.43	2.23	20	1.88	732	2	0.70	18	670	36	<5	<20	197	0.13	<10	126	<10	8	7
236	S07-19381	1.2	6.41	10	785	<5	3.27	<1	9	156	55	2.79	2.28	20	1.82	865	1	0.59	12	550	164	<5	<20	203	0.12	<10	88	<10	7	5
237	S07-19382	1.0	7.22	20	200	<5	2.56	<1	12	322	71	4.07	2.29	20	1.42	758	4	0.37	15	880	102	<5	<20	185	0.13	<10	77	<10	10	9
238	S07-19383	0.8	8.12	10	710	<5	2.45	<1	13	84	88	4.10	2.11	20	1.61	891	9	1.45	13	820	54	<5	<20	205	0.17	<10	125	<10	8	10
239	S07-19384	0.6	5.89	10	375	<5	2.20	<1	9	166	66	2.83	1.95	20	1.05	732	12	2.00	22	720	32	<5	<20	199	0.15	<10	189	<10	7	9
240	S07-19385	0.4	6.98	15	280	<5	2.63	<1	11	160	77	3.44	2.66	20	1.22	1001	6	1.52	14	910	30	<5	<20	210	0.16	<10	121	<10	8	6
241	S07-19386	1.4	7.17	25	255	<5	2.65	<1	10	164	79	4.00	2.76	20	1.38	1018	6	0.92	19	740	32	<5	<20	212	0.16	<10	109	<10	7	6
242	S07-19387	1.0	7.45	10	415	<5	3.30	<1	12	148	80	4.43	3.57	20	2.00	1185	2	0.33	15	1020	42	<5	<20	244	0.18	<10	108	<10	9	9
243	S07-19388	7.2	6.86	5	390	<5	3.71	2	14	142	117	4.54	3.30	20	2.14	1456	4	0.28	14	1270	2942	<5	<20	312	0.17	<10	201	<10	9	14
244	S07-19389	1.0	5.81	15	330	<5	2.09	<1	13	157	88	4.06	2.82	20	1.27	776	17	0.29	29	820	44	<5	<20	168	0.14	<10	223	<10	8	6
245	S07-19390	5.0	4.50	195	225	<5	0.52	1	11	38	572	5.08	2.80	10	1.81	392	7	0.23	24	540	106	50	<20	75	0.27	<10	55	<10	11	60
246	S07-19391	0.6	7.58	5	1350	<5	1.64	<1	15	160	50	4.58	3.64	20	2.05	908	<1	0.63	26	1030	36	<5	<20	147	0.19	<10	126	<10	7	9
247	S07-19392	0.8	6.97	15	490	<5	2.40	<1	17	176	88	5.18	3.51	20	1.52	1004	10	0.30	32	1390	62	<5	<20	205	0.15	<10	224	<10	11	6
248	S07-19393	0.4	6.60	<5	930	<5	3.08	<1	14	148	64	4.16	3.06	20	1.75	1123	4	0.46	21	1980	42	<5	<20	226	0.16	<10	112	<10	11	9
249	S07-19394	0.4	8.24	5	1210	<5	2.69	<1	17	47	49	5.06	3.68	20	2.16	1330	<1	0.55	16	1320	36	<5	<20	203	0.19	<10	128	<10	7	9
250	S07-19395	0.4	7.00	5	905	<5	3.08	<1	12	86	41	4.29	3.08	20	1.67	1378	4	0.69	10	1640	30	<5	<20	226	0.18	<10	85	<10	11	8
251	S07-19396	0.6	8.19	5	860	<5	3.29	<1	12	54	39	4.88	3.43	20	2.20	1371	<1	0.47	11	1520	32	<5	<20	217	0.19	<10	112	<10	10	9
252	S07-19397	0.6	7.34	<5	930	<5	3.31	<1	8	122	68	4.21	3.27	20	1.90	1304	<1	0.36	10	1120	48	<5	<20	247	0.19	<10	96	<10	10	10
253	S07-19398	0.6	8.44	10	890	<5	4.50	<1	17	89	51	5.15	3.41	10	2.54	1658	<1	0.76	18	1230	38	<5	<20	296	0.20	<10	179	<10	7	7
254	S07-19399	0.6	8.78	10	795	<5	3.90	<1	19	67	62	5.34	3.41	20	2.17	1242	<1	1.46	15	1180	34	<5	<20	309	0.18	<10	165	<10	7	8
255	S07-19400	0.4	6.88	15	360	<5	3.90	<1	12	145	34	4.43	3.18	20	1.86	1492	<1	0.52	15	1120	34	<5	<20	386	0.14	<10	112	<10	9	8
256	S07-19401	0.8	8.25	20	560	<5	3.46	<1	16	96	53	5.81	4.10	20	2.04	1403	<1	0.41	18	1450	92	<5	<20	310	0.18	<10	130	<10	10	11

QC DATA:**Repeat:**

1	S07-19146	0.2	5.21	10	1780	<5	0.77	<1	4	46	21	1.77	1.91	10	1.13	2021	<1	0.71	14	240	24	<5	<20	81	0.11	<10	27	<10	5	6
10	S07-19155	0.4	6.11	10	1800	<5	0.94	<1	14	83	75	2.77	1.95	20	2.06	2608	<1	0.39	27	620	32	<5	<20	95	0.15	<10	84	<10	8	7
19	S07-19164	0.2	6.14	10	2315	<5	0.81	<1	8	50	15	2.18	2.39	20	1.54	1979	<1	0.74	20	290	28	<5	<20	93	0.16	<10	34	<10	6	6
36	S07-19181	0.2	5.38	20	855	<5	2.72	<1	24	385	86	2.78	2.29	10	4.63	1456	<1	0.43	170	480	26	10	<20	204	0.09	<10	97	<10	7	6
45	S07-19190	<0.2	5.54	30	1500	<5	2.05	<1	15	156	4	2.83	2.32	20	2.91	1863	2	0.14	106	490	36	<5	<20	210	0.12	<10	81	<10	9	4
54	S07-19199	<0.2	4.99	40	1130	<5	3.74	<1	32	457	84	4.44	2.01	<10	4.61	2486	<1	0.35	193	670	35	5	<20	307	0.09	<10	151	<10	5	9
71	S07-19216	0.4	6.20	<5	1900	<5	1.31	<1	9	299	48	2.95	2.63	20	1.60	2331	<1	0.69	22	680	32	<5	<20	137	0.15	<10	56	<10	8	6
80	S07-19225	2.0	3.38	5	355	<5	5.27	<1	39	482	672	5.24	1.45	<10	6.01	2623	<1	0.19	190	820	22	10	<20	354	0.04	<10	142	<10	4	8
89	S07-19234	0.8	5.79	<5	1705	<5	0.80	<1	18	257	158	4.67	2.11	20	2.01	2096	<1	1.23	44	620	40	<5	<20	101	0.17	<10	88	<10	7	8

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Z
107	S07-19252	0.8	5.00	10	1125	<5	2.04	<1	21	211	189	4.01	2.11	10	2.80	2620	<1	0.28	61	690	34	5	<20	211	0.11	<10	139	<10	7	9
115	S07-19260	0.4	4.89	5	1085	<5	2.03	<1	11	148	40	2.34	1.99	20	2.17	2300	<1	0.83	50	430	28	<5	<20	167	0.10	<10	65	<10	10	5
124	S07-19269	0.2	5.67	<5	955	<5	0.28	<1	6	52	2	2.44	2.97	10	3.63	655	<1	0.26	29	400	30	<5	<20	43	0.14	<10	79	<10	6	4
141	S07-19286	0.2	4.36	15	220	<5	5.91	<1	34	576	11	5.54	2.20	<10	8.51	2620	<1	0.27	221	770	24	10	<20	288	0.04	<10	148	<10	5	9
150	S07-19295	0.4	4.75	25	265	<5	4.11	<1	33	420	16	4.27	1.85	<10	6.56	1624	<1	0.20	302	530	32	5	<20	183	0.08	<10	75	<10	7	8
159	S07-19304	1.0	4.46	10	160	<5	3.72	6	14	243	74	5.20	2.25	20	1.58	1004	47	0.09	89	880	80	5	<20	162	0.10	<10	297	<10	6	51
176	S07-19321	1.2	4.15	75	185	<5	5.12	12	44	821	35	5.16	1.96	<10	6.15	2578	1	0.23	311	550	108	10	<20	418	0.05	<10	128	<10	4	102
185	S07-19330	0.4	4.78	20	165	<5	5.24	<1	30	308	56	5.70	2.03	<10	6.21	1203	<1	0.40	114	940	22	10	<20	234	0.10	<10	167	<10	6	5
194	S07-19339	0.8	4.01	20	210	<5	3.41	<1	20	346	4	4.05	0.86	10	4.17	1544	<1	0.70	120	420	14	<5	<20	196	0.07	<10	64	<10	6	4
211	S07-19356	2.0	5.00	20	235	<5	4.43	1	20	334	67	4.35	2.80	20	3.01	1206	22	0.20	88	760	48	10	<20	249	0.09	<10	235	<10	8	9
220	S07-19365	0.5	7.07	10	815	<5	4.88	<1	8	137	85	3.62	2.29	20	2.13	1437	6	0.32	9	1160	34	<5	<20	251	0.13	<10	71	<10	10	7
229	S07-19374	0.4	6.14	20	310	<5	3.24	1	14	169	80	3.85	2.34	20	1.62	821	13	0.56	32	1170	38	<5	<20	168	0.12	<10	226	<10	6	11
246	S07-19391	0.8	7.83	5	1335	<5	1.72	<1	15	145	50	4.59	3.61	20	2.05	927	<1	0.62	26	1050	36	<5	<20	148	0.19	<10	127	<10	7	9

Resplit:

1	S07-19146	<0.2	5.25	10	1790	<5	0.66	<1	4	53	22	1.81	1.94	10	1.11	2127	<1	0.75	13	260	24	<5	<20	81	0.12	<10	31	<10	7	7
36	S07-19181	0.2	5.32	15	795	<5	2.93	<1	28	405	110	2.99	2.05	10	5.06	1573	<1	0.42	181	510	30	15	<20	226	0.08	<10	99	<10	7	6
71	S07-19216	0.2	6.60	<5	2015	<5	1.21	<1	12	272	51	2.96	2.72	20	1.68	2572	<1	0.73	23	700	40	<5	<20	129	0.16	<10	61	<10	7	6
107	S07-19252	0.6	4.68	5	1075	<5	2.15	<1	21	174	183	3.95	1.94	10	2.65	2562	<1	0.26	61	660	38	<5	<20	194	0.12	<10	137	<10	6	8
141	S07-19286	0.2	4.16	15	215	<5	5.73	<1	33	542	12	5.23	2.10	<10	8.10	2547	<1	0.27	223	740	28	10	<20	271	0.06	<10	142	<10	5	8
176	S07-19321	1.2	3.76	60	175	<5	4.71	28	40	842	40	5.29	1.72	<10	6.17	2467	3	0.22	307	540	116	10	<20	438	0.05	<10	121	<10	3	114
211	S07-19356	2.2	5.04	20	235	<5	4.25	1	20	282	64	5.06	2.79	20	2.77	1163	25	0.20	90	800	48	10	<20	219	0.08	<10	227	<10	8	9
246	S07-19391	0.6	7.61	<5	1320	<5	1.71	<1	15	140	49	4.74	3.68	20	2.20	992	<1	0.65	25	1040	42	<5	<20	162	0.18	<10	129	<10	7	8

Standard:

Stsd3		0.5	5.82	30	1290	<5	2.50	<1	16	62	36	3.93	1.57	30	1.40	2667	5	1.21	34	1770	62	<5	<20	236	0.34	<10	114	<10	29	20
Stsd3		0.4	5.75	30	1325	<5	2.51	<1	16	61	38	3.97	1.41	40	1.44	2627	5	1.28	35	1730	52	<5	<20	244	0.38	<10	119	<10	29	20
Stsd3		0.6	5.92	25	1355	<5	2.70	<1	15	61	40	4.29	1.52	40	1.41	2610	5	1.22	34	1770	52	5	<20	254	0.32	<10	112	<10	29	20
Stsd3		0.6	5.66	20	1340	<5	2.72	<1	15	65	38	4.38	1.51	40	1.49	2615	5	1.19	35	1670	60	5	<20	254	0.34	<10	127	<10	30	20
Stsd3		0.6	5.60	25	1340	<5	2.66	<1	15	62	37	4.13	1.40	40	1.30	2501	5	1.30	35	1650	58	<5	<20	257	0.34	<10	120	<10	30	21
Stsd3		0.6	5.70	20	1275	<5	2.53	<1	15	58	37	4.13	1.45	30	1.38	2552	5	1.18	33	1720	53	<5	<20	248	0.32	<10	107	<10	28	19
Stsd3		0.5	5.74	20	1280	<5	2.61	<1	15	57	38	3.99	1.50	40	1.40	2501	5	1.16	32	1600	54	<5	<20	233	0.30	<10	107	<10	28	20
Stsd3		0.6	5.73	20	1295	<5	2.50	<1	15	59	39	4.14	1.55	40	1.43	2559	5	1.20	32	1730	56	<5	<20	237	0.30	<10	108	<10	28	20

ICP: 4 ACID DIGEST/ICP-FINISH


AG: 4 ACID DIGEST/AA-FINISH

JJ/nw

df/td2283as/td2283bs/td2283cs

XLS/07

Jutta Jealouse
ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2290

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

11-Mar-08

Attention: Bob Singh

No. of samples received: 183

Sample Type: Core

Project: Spanish Mountain


Shipment #: SMC-07-154

Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-34497	<0.03	<0.001
2	S07-34498	<0.03	<0.001
3	S07-34499	<0.03	<0.001
4	S07-34500	<0.03	<0.001
5	S07-34501	<0.03	<0.001
6	S07-34502	<0.03	<0.001
7	S07-34504	<0.03	<0.001
8	S07-34505	<0.03	<0.001
9	S07-34506	<0.03	<0.001
10	S07-34507	<0.03	<0.001
11	S07-34508	<0.03	<0.001
12	S07-34509	<0.03	<0.001
13	S07-34510	<0.03	<0.001
14	S07-34511	<0.03	<0.001
15	S07-34512	<0.03	<0.001
16	S07-34513	<0.03	<0.001
17	S07-34514	<0.03	<0.001
18	S07-34515	<0.03	<0.001
19	S07-34516	<0.03	<0.001
20	S07-34517	<0.03	<0.001
21	S07-34518	<0.03	<0.001
22	S07-34519	<0.03	<0.001
23	S07-34520	<0.03	<0.001
24	S07-34521	<0.03	<0.001
25	S07-34522	<0.03	<0.001
26	S07-34523	2.04	0.059
27	S07-34524	<0.03	<0.001
28	S07-34525	<0.03	<0.001


* = 30g FA


ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	S07-34526	<0.03	<0.001
30	S07-34527	<0.03	<0.001
31	S07-34528	<0.03	<0.001
32	S07-34529	<0.03	<0.001
33	S07-34530	<0.03	<0.001
34	S07-34531	<0.03	<0.001
35	S07-34532	<0.03	<0.001
36	S07-34533	<0.03	<0.001
37	S07-34534	<0.03	<0.001
38	S07-34535	<0.03	<0.001
39	S07-34536	0.05	0.002
40	S07-34537	<0.03	<0.001
41	S07-34538	<0.03	<0.001
42	S07-34539	<0.03	<0.001
43	S07-34540	* <0.03	<0.001
44	S07-34541	<0.03	<0.001
45	S07-34542	<0.03	<0.001
46	S07-34543	<0.03	<0.001
47	S07-34544	<0.03	<0.001
48	S07-34545	<0.03	<0.001
49	S07-34546	<0.03	<0.001
50	S07-34547	<0.03	<0.001
51	S07-34548	<0.03	<0.001
52	S07-34549	<0.03	<0.001
53	S07-34550	<0.03	<0.001
54	S07-34551	<0.03	<0.001
55	S07-34552	<0.03	<0.001
56	S07-34553	<0.03	<0.001
57	S07-34554	<0.03	<0.001
58	S07-34555	<0.03	<0.001
59	S07-34556	<0.03	<0.001
60	S07-34557	<0.03	<0.001
61	S07-34558	0.08	0.002
62	S07-34559	39.0	1.138
63	S07-34560	* 6.71	0.196
64	S07-34561	0.08	0.002
65	S07-34562	<0.03	<0.001
66	S07-34563	0.14	0.004
67	S07-34564	0.02	0.001
68	S07-34565	8.85	0.258
69	S07-34566	1.23	0.036
70	S07-34567	<0.03	<0.001
71	S07-34568	<0.03	<0.001
72	S07-34569	<0.03	<0.001
73	S07-34570	<0.03	<0.001


* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
74	S07-34571	<0.03	<0.001
75	S07-34572	<0.03	<0.001
76	S07-34573	<0.03	<0.001
77	S07-34574	<0.03	<0.001
78	S07-34575	<0.03	<0.001
79	S07-34576	1.03	0.030
80	S07-34577	<0.03	<0.001
81	S07-34578	<0.03	<0.001
82	S07-34579	<0.03	<0.001
83	S07-34580	<0.03	<0.001
84	S07-34581	0.14	0.004
85	S07-34582	0.22	0.007
86	S07-34583	0.15	0.004
87	S07-34584	0.18	0.005
88	S07-34585	0.24	0.007
89	S07-34586	0.29	0.008
90	S07-34587	0.15	0.004
91	S07-34588	0.16	0.005
92	S07-34589	0.59	0.017
93	S07-34590	0.44	<0.001
94	S07-34591	0.18	0.005
95	S07-34592	0.15	0.004
96	S07-34593	0.07	0.002
97	S07-34594	0.12	0.003
98	S07-34595	0.21	0.006
99	S07-34596	0.14	0.004
100	S07-34597	1.06	0.031
101	S07-34598	0.43	0.012
102	S07-34599	0.04	0.001
103	S07-34600	0.05	0.001
104	S07-34601	0.49	0.014
105	S07-34602	<0.03	<0.001
106	S07-34603	0.04	0.001
107	S07-34604	0.30	0.009
108	S07-34605	0.20	0.006
109	S07-34606	0.50	0.015
110	S07-34607	0.08	0.002
111	S07-34608	0.11	0.003
112	S07-34609	0.47	0.014
113	S07-34610	1.57	0.046
114	S07-34611	0.42	0.012
115	S07-34612	<0.03	<0.001
116	S07-34613	0.47	0.014
117	S07-34614	1.17	0.034
118	S07-34615	0.51	0.015


* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
119	S07-34616	0.29	0.008
120	S07-34617	0.04	0.001
121	S07-34618	1.14	0.033
122	S07-34619	0.05	0.002
123	S07-34620	0.04	0.001
124	S07-34621	<0.03	<0.001
125	S07-34622	0.05	0.001
126	S07-34623	<0.03	<0.001
127	S07-34624	* 2.08	0.061
128	S07-34625	<0.03	<0.001
129	S07-34626	0.18	0.005
130	S07-34627	0.40	0.012
131	S07-34628	0.52	0.015
132	S07-34629	0.91	0.027
133	S07-34630	<0.03	<0.001
134	S07-34631	0.15	0.004
135	S07-34632	0.38	0.011
136	S07-34633	0.08	0.002
137	S07-34634	0.03	0.001
138	S07-34635	0.04	0.001
139	S07-34636	0.08	0.002
140	S07-34637	0.18	0.005
141	S07-34638	0.05	0.001
142	S07-34639	0.06	0.002
143	S07-34640	0.14	0.004
144	S07-34641	0.04	0.001
145	S07-34642	0.09	0.003
146	S07-34643	0.27	0.008
147	S07-34644	0.21	0.006
148	S07-34645	0.47	0.014
149	S07-34646	0.08	0.002
150	S07-34647	0.63	0.018
151	S07-34648	* <0.03	<0.001
152	S07-34649	0.08	0.002
153	S07-34650	0.05	0.002
154	S07-34651	0.04	0.001
155	S07-34652	1.87	0.054
156	S07-34653	0.21	0.006
157	S07-34654	0.39	0.011
158	S07-34655	0.25	0.007
159	S07-34656	0.10	0.003
160	S07-34657	0.24	0.007
161	S07-34658	<0.03	<0.001
162	S07-34659	1.14	0.033
163	S07-34660	* 6.64	0.194

* = 30g FA


 ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
164	S07-34661	0.07	0.002
165	S07-34662	0.03	0.001
166	S07-34663	<0.03	<0.001
167	S07-34664	0.07	0.002
168	S07-34665	0.29	0.009
169	S07-34666	0.29	0.009
170	S07-34667	<0.03	<0.001
171	S07-34668	0.10	0.003
172	S07-34669	0.32	0.009
173	S07-34670	0.43	0.013
174	S07-34671	0.05	0.001
175	S07-34672	0.08	0.002
176	S07-34673	0.19	0.005
177	S07-34674	0.68	0.020
178	S07-34675	0.44	0.013
179	S07-34676	0.98	0.029
180	S07-34677	3.77	0.110
181	S07-34678	0.91	0.027
182	S07-34679	0.06	0.002
183	S07-34680	0.20	0.006

QC DATA:

Resplit:

1	S07-34497	<0.03	<0.001
36	S07-34533	<0.03	<0.001
71	S07-34568	<0.03	<0.001
106	S07-34603	0.03	0.001
141	S07-34638	0.12	0.003
176	S07-34673	0.17	0.005


Standard:

OXI54	1.89	0.055
OXI54	1.90	0.055
OXI54	1.88	0.055
OXI54	1.81	0.053
OXI54	1.88	0.055
OXI54	1.84	0.054
OXI54	1.90	0.055
OXI54	1.85	0.054
OXI54	1.90	0.055
OXI54	1.90	0.055
OXI54	1.90	0.055
OXI54	1.88	0.055
OXI54	1.82	0.053

KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw
XLS/07


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

ECH LABORATORY LTD.

Dallas Drive

NANAIMO, B.C.

4

250-573-5700

250-573-4557

ICP CERTIFICATE OF ANALYSIS A-07-2290

Skygold Ventures

615 - 800 W. Pender Street

Vancouver, BC

V6B 2V6

No. of samples received: 183

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-154

Samples submitted by: Tasha Gainer

in ppm unless otherwise reported

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
S07-34497	1.2	4.46	55	715	<5	0.51	<1	20	151	102	3.78	0.99	20	0.25	2009	1	1.61	41	400	28	<5	<20	67	0.13	<10	44	<10	8	74
S07-34498	0.6	3.19	25	440	<5	0.34	<1	10	140	41	3.10	0.65	10	0.18	1722	1	0.98	34	280	26	<5	<20	50	0.09	<10	35	<10	5	56
S07-34499	0.6	3.30	65	465	<5	0.49	<1	18	271	99	3.17	0.67	10	0.62	1435	1	0.50	72	290	32	<5	<20	59	0.11	<10	39	<10	7	47
S07-34500	0.2	5.21	150	315	<5	7.75	<1	41	886	3	6.67	0.62	<10	5.30	2553	<1	0.83	271	750	22	10	<20	363	0.03	<10	143	<10	5	137
S07-34501	0.2	4.80	165	225	<5	6.52	<1	44	720	3	5.70	1.14	<10	5.75	2207	<1	0.94	306	770	20	10	<20	350	0.03	<10	136	<10	4	101
S07-34502	0.2	4.89	90	1240	<5	2.14	<1	12	159	15	2.09	1.76	20	1.60	1444	<1	0.46	71	320	30	<5	<20	142	0.09	<10	57	<10	8	33
S07-34504	0.4	3.68	25	935	<5	2.14	<1	15	268	81	2.87	1.29	10	1.69	1800	<1	0.25	52	410	32	5	<20	148	0.07	<10	76	<10	4	64
S07-34505	0.4	5.07	25	1750	<5	1.50	<1	15	172	88	2.50	2.06	10	1.68	1566	<1	0.17	43	430	24	<5	<20	124	0.11	<10	114	<10	5	47
S07-34506	0.4	5.57	40	1390	<5	4.12	<1	26	406	28	4.52	1.82	10	4.84	2433	<1	0.62	150	860	26	5	<20	352	0.10	<10	112	<10	7	64
S07-34507	0.2	5.86	45	1025	<5	5.64	<1	36	522	41	5.72	1.84	<10	6.56	1807	<1	0.88	233	1000	24	10	<20	510	0.06	<10	156	<10	5	55
S07-34508	0.2	5.45	35	850	<5	2.65	<1	31	278	100	4.37	1.26	20	3.17	1785	<1	1.20	133	590	36	5	<20	228	0.14	<10	112	<10	6	70
S07-34509	<0.2	7.33	10	490	<5	3.14	<1	11	81	36	4.57	1.07	10	1.34	800	3	2.84	28	860	28	<5	<20	372	0.37	<10	108	<10	17	53
S07-34510	0.4	4.02	20	700	<5	3.08	<1	29	374	29	4.43	1.01	10	3.99	2865	<1	0.63	207	500	30	5	<20	259	0.10	<10	130	<10	5	103
S07-34511	0.2	4.69	15	795	<5	1.15	<1	26	149	49	4.13	1.06	20	1.67	2254	<1	1.27	84	540	36	<5	<20	124	0.14	<10	75	<10	6	84
S07-34512	0.2	5.06	10	1150	<5	1.32	<1	26	123	48	4.43	1.38	20	1.50	2681	<1	1.34	69	540	38	<5	<20	128	0.16	<10	80	<10	6	85
S07-34513	0.8	4.24	10	1010	<5	1.30	<1	21	147	172	3.83	0.95	20	1.66	2307	<1	1.11	52	470	36	<5	<20	126	0.11	<10	109	<10	5	104
S07-34514	0.8	5.62	15	1520	<5	1.20	<1	12	119	103	3.08	0.95	20	1.85	1780	<1	1.04	38	370	50	<5	<20	131	0.10	<10	51	<10	8	80
S07-34515	1.0	6.19	20	1720	<5	1.03	<1	17	93	139	3.31	1.04	20	1.98	1781	<1	1.11	46	410	36	<5	<20	120	0.11	<10	59	<10	8	88
S07-34516	0.8	4.18	95	705	<5	3.36	<1	35	470	9	4.72	0.82	<10	4.44	2375	<1	0.14	283	640	78	5	<20	274	0.06	<10	118	<10	5	57
S07-34517	0.8	4.46	35	750	<5	2.45	<1	30	221	119	4.36	0.89	20	3.13	2343	<1	0.66	133	580	28	<5	<20	184	0.11	<10	125	<10	6	67
S07-34518	0.6	4.39	20	710	<5	1.07	<1	23	65	67	3.96	1.02	20	1.36	2420	<1	1.00	65	430	32	<5	<20	94	0.12	<10	56	<10	6	69
S07-34519	0.4	4.63	15	950	<5	1.69	<1	32	64	53	3.73	0.97	20	1.49	2518	<1	0.70	61	490	36	<5	<20	130	0.14	<10	84	<10	7	79
S07-34520	0.4	5.69	10	1065	<5	1.22	<1	25	62	52	5.08	1.07	30	1.51	3378	<1	1.19	71	530	40	<5	<20	99	0.17	<10	85	<10	8	113
S07-34521	0.6	5.22	10	1220	<5	0.96	<1	14	47	160	3.22	1.10	20	1.59	2762	<1	0.89	35	400	26	<5	<20	83	0.12	<10	110	<10	7	88
S07-34522	0.4	5.68	5	1500	<5	0.83	<1	6	21	8	1.82	0.97	10	1.34	1942	<1	0.81	14	240	22	<5	<20	82	0.11	<10	71	<10	8	69

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La %	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
S07-34523	5.1	4.66	100	275	<5	0.50	2	11	39	595	5.46	2.12	10	1.79	385	7	0.25	24	520	100	45	<20	74	0.28	<10	53	<10	11	670
S07-34524	0.8	4.12	15	520	<5	1.20	<1	19	300	123	3.75	0.85	20	2.22	2511	<1	1.12	76	350	32	<5	<20	90	0.10	<10	50	<10	6	80
S07-34525	0.6	4.50	45	685	<5	2.47	<1	35	546	4	3.81	0.87	10	4.29	3453	<1	0.49	326	410	22	10	<20	168	0.06	<10	70	<10	6	106
S07-34526	0.4	5.87	5	1185	<5	1.01	<1	5	53	28	1.97	1.14	10	1.30	1746	<1	1.19	12	330	26	<5	<20	97	0.11	<10	36	<10	9	65
S07-34527	0.8	6.87	5	1245	<5	0.90	<1	4	70	36	2.01	1.21	20	1.39	1237	<1	1.53	9	380	26	<5	<20	104	0.15	<10	21	<10	10	34
S07-34528	0.4	4.01	25	365	<5	3.41	<1	30	590	7	4.00	0.84	<10	5.83	1785	<1	0.36	277	400	18	10	<20	228	0.05	<10	65	<10	6	70
S07-34529	1.0	3.85	25	340	<5	3.39	<1	29	655	38	3.73	0.88	<10	5.95	1396	<1	0.19	224	410	18	25	<20	231	0.04	<10	75	<10	5	49
S07-34530	1.2	3.90	30	350	<5	3.32	<1	28	726	46	3.67	0.89	<10	5.71	1322	<1	0.21	222	370	16	20	<20	221	0.05	<10	75	<10	6	46
S07-34531	0.6	3.97	65	160	<5	5.37	<1	46	848	32	5.28	0.78	<10	8.43	1527	<1	0.43	409	550	20	15	<20	329	0.03	<10	103	<10	5	54
S07-34532	0.4	3.97	100	370	<5	5.70	<1	37	703	26	4.88	0.77	<10	7.50	1533	<1	0.24	351	600	18	15	<20	390	0.04	<10	91	<10	6	45
S07-34533	0.6	4.44	50	665	<5	3.55	<1	27	590	31	4.09	1.14	10	5.74	1299	<1	0.24	258	460	30	10	<20	235	0.09	<10	64	<10	7	72
S07-34534	0.4	4.13	40	135	<5	4.78	<1	42	821	24	5.24	0.84	<10	9.18	1451	<1	0.57	417	600	14	15	<20	296	0.06	<10	102	<10	6	44
S07-34535	0.2	5.84	10	1290	<5	0.72	<1	4	134	17	1.59	1.57	20	1.28	535	<1	0.40	19	250	26	<5	<20	65	0.13	<10	22	<10	9	35
S07-34536	0.6	4.89	15	1085	<5	1.91	<1	6	131	19	1.54	1.15	20	1.25	1008	<1	0.37	27	250	36	<5	<20	124	0.10	<10	40	<10	8	124
S07-34537	0.6	6.42	10	1270	<5	0.90	<1	6	87	67	1.90	1.51	30	1.41	577	<1	0.89	13	330	28	<5	<20	68	0.12	<10	30	<10	10	34
S07-34538	0.4	5.38	25	270	<5	4.26	<1	25	417	8	3.87	0.88	20	5.97	1407	1	1.06	232	530	22	<5	<20	168	0.07	<10	61	<10	9	48
S07-34539	0.4	3.64	50	105	<5	7.05	<1	46	837	35	5.21	0.80	<10	9.13	1705	<1	0.26	455	530	14	15	<20	371	0.02	<10	100	<10	6	55
S07-34540	<0.2	0.08	<5	5	<5	>10	<1	<1	2	<1	0.05	<0.01	<10	1.72	28	<1	0.01	32	40	<2	<5	<20	6047	<0.01	<10	2	<10	<1	4
S07-34541	0.2	3.95	50	45	<5	6.49	<1	54	937	30	5.82	0.99	<10	9.70	1612	<1	0.31	565	600	14	10	<20	261	0.02	<10	110	<10	5	64
S07-34542	0.4	4.50	35	80	<5	5.09	<1	46	845	41	5.65	1.04	<10	7.65	1589	<1	0.48	439	610	18	15	<20	246	0.05	<10	113	<10	6	60
S07-34543	<0.2	4.86	25	40	<5	3.29	<1	32	642	14	5.24	0.68	<10	7.16	1253	<1	0.80	300	600	20	10	<20	174	0.06	<10	88	<10	6	50
S07-34544	0.4	3.65	70	130	<5	6.02	3	52	892	15	5.21	1.03	<10	8.34	1752	<1	0.30	522	480	16	15	<20	288	0.02	<10	99	<10	5	387
S07-34545	<0.2	4.05	15	50	<5	4.12	<1	40	662	14	4.55	0.80	<10	7.22	1098	<1	0.36	355	490	14	10	<20	170	0.04	<10	88	<10	6	57
S07-34546	0.4	5.36	30	260	<5	5.07	<1	24	338	79	3.89	1.06	<10	5.73	1103	<1	0.67	150	650	18	<5	<20	246	0.08	<10	89	<10	8	27
S07-34547	0.4	4.46	30	170	<5	3.33	<1	27	448	4	4.40	1.12	10	6.32	1260	<1	0.54	221	610	18	10	<20	171	0.06	<10	102	<10	7	38
S07-34548	0.2	3.53	25	275	<5	3.80	<1	18	264	25	2.52	1.27	10	3.06	884	3	0.31	97	570	20	5	<20	171	0.06	<10	44	<10	7	33
S07-34549	0.6	5.60	10	705	<5	0.58	<1	7	107	72	2.26	1.60	10	1.44	438	<1	1.22	19	280	28	<5	<20	66	0.11	<10	24	<10	8	54
S07-34550	0.4	5.42	25	780	<5	2.94	<1	18	383	11	3.44	1.21	10	3.62	2076	<1	0.68	157	440	24	5	<20	176	0.09	<10	68	<10	8	59
S07-34551	0.2	5.98	5	1135	<5	1.08	<1	3	60	6	1.55	1.67	20	1.45	924	<1	0.43	10	320	24	<5	<20	87	0.12	<10	25	<10	10	31
S07-34552	0.4	7.75	10	1445	<5	1.14	<1	5	46	13	1.83	1.90	30	1.48	799	<1	0.32	15	240	32	<5	<20	100	0.16	<10	37	<10	8	40
S07-34553	0.2	6.34	10	1070	<5	0.49	<1	4	62	28	1.69	1.59	20	1.13	450	<1	0.80	12	250	30	<5	<20	59	0.14	<10	20	<10	9	47
S07-34554	<0.2	5.36	20	570	<5	3.60	<1	22	286	8	3.97	1.15	10	4.13	1522	<1	0.60	91	460	22	<5	<20	227	0.09	<10	104	<10	7	42
S07-34555	0.4	4.61	45	330	<5	5.02	<1	37	566	23	4.78	1.07	<10	5.71	1796	<1	0.42	272	470	22	10	<20	319	0.06	<10	99	<10	5	69
S07-34556	0.4	5.66	10	625	<5	0.68	<1	5	66	46	2.12	1.62	10	1.31	914	<1	1.52	14	260	24	<5	<20	84	0.13	<10	21	<10	9	32
S07-34557	<0.2	6.47	25	800	<5	1.44	<1	11	207	12	2.72	1.44	10	2.51	1504	<1	0.87	71	480	22	<5	<20	116	0.15	<10	45	<10	12	52
S07-34558	<0.2	3.43	20	445	<5	2.76	2	8	232	3	2.23	1.24	<10	2.38	1530	<1	0.08	71	340	16	<5	<20	296	0.06	<10	41	<10	6	206
S07-34559	2.0	5.89	60	645	<5	3.10	3	25	422	3	4.19	1.37	10	4.57	2406	<1	0.32	239	690	110	<5	<20	213	0.12	<10	90	<10	9	377
S07-34560	6.2	3.92	160	325	<5	0.46	<1	7	48	53	3.53	2.97	<10	0.27	253	7	0.50	22	450	30	70	<20	105	0.30	<10	53	<10	10	50
S07-34561	0.2	5.98	5	860	<5	0.74	<1	5	41	17	1.74	1.80	10	1.63	732	<1	0.64	10	310	24	<5	<20	75	0.14	<10	22	<10	6	38
S07-34562	0.4	7.12	10	1045	<5	1.93	<1	7	79	36	2.15	1.74	20	1.71	656	<1	0.26	19	250	30	<5	<20	144	0.17	<10	40	<10	6	27

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La %	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
S07-34563	0.6	4.08	20	490	<5	3.03	<1	10	328	9	2.67	1.33	10	2.37	1000	<1	0.12	50	120	308	5	<20	230	0.09	<10	33	<10	9	85
S07-34564	0.2	4.15	45	175	<5	5.17	<1	36	622	3	4.72	1.13	<10	7.07	1892	<1	0.33	277	460	18	5	<20	278	0.05	<10	86	<10	5	94
S07-34565	4.6	3.60	115	155	<5	6.69	<1	47	759	40	4.63	1.00	<10	7.40	2106	<1	0.31	481	430	780	15	<20	337	0.05	<10	91	<10	6	66
S07-34566	0.6	4.34	10	590	<5	1.89	<1	6	132	65	1.76	1.19	10	1.29	831	<1	0.61	21	310	192	<5	<20	139	0.11	<10	42	<10	5	47
S07-34567	0.6	5.07	35	670	<5	2.96	<1	16	247	14	2.36	1.21	20	3.43	961	<1	0.33	155	350	40	<5	<20	172	0.11	<10	48	<10	9	66
S07-34568	0.4	3.96	70	25	<5	7.59	<1	46	639	22	5.65	0.37	<10	9.27	1892	<1	0.46	419	660	18	5	<20	335	0.06	<10	113	<10	7	75
S07-34569	0.2	4.13	45	35	<5	5.37	<1	42	736	27	5.34	0.53	<10	8.79	1385	<1	0.48	354	560	20	10	<20	235	0.03	<10	103	<10	5	69
S07-34570	0.2	3.86	65	35	<5	4.91	<1	41	652	22	4.83	0.50	<10	8.23	1319	<1	0.45	332	530	18	10	<20	233	0.03	<10	98	<10	5	66
S07-34571	0.2	5.18	70	195	<5	2.74	<1	32	619	20	5.10	1.01	<10	7.26	1237	<1	0.38	301	660	20	10	<20	183	0.07	<10	94	<10	6	81
S07-34572	0.4	4.53	70	280	<5	4.53	<1	35	625	13	4.26	0.98	<10	5.98	1522	<1	0.31	353	550	18	10	<20	409	0.07	<10	76	<10	7	57
S07-34573	0.4	5.54	80	305	<5	2.19	<1	38	534	29	4.95	1.05	<10	6.77	1141	<1	0.48	305	680	20	10	<20	150	0.10	<10	102	<10	6	77
S07-34574	1.0	4.04	85	135	<5	4.65	<1	42	732	71	4.48	1.00	<10	6.78	1588	<1	0.46	375	560	24	15	<20	262	0.04	<10	99	<10	4	51
S07-34575	0.4	4.68	60	280	<5	4.20	<1	38	668	72	4.38	1.14	<10	6.48	1468	<1	0.34	332	500	28	10	<20	228	0.06	<10	90	<10	5	53
S07-34576	11.4	4.33	50	195	<5	5.19	<1	46	943	227	5.58	1.13	<10	7.28	2040	1	0.30	375	530	38	115	<20	303	0.04	<10	126	<10	5	109
S07-34577	0.6	5.52	35	310	<5	4.08	<1	20	335	113	4.24	1.50	20	3.27	1234	16	0.17	131	770	38	<5	<20	220	0.11	<10	171	<10	8	78
S07-34578	<0.2	0.04	<5	10	<5	>10	<1	<1	2	2	0.03	<0.01	<10	1.97	26	<1	0.01	19	40	2	<5	<20	6050	<0.01	<10	2	<10	<1	3
S07-34579	0.4	4.65	50	370	<5	3.43	<1	33	619	85	5.13	1.19	10	5.08	1473	5	0.18	210	740	36	10	<20	207	0.08	<10	147	<10	6	141
S07-34580	0.4	4.56	60	305	<5	5.07	<1	35	632	53	5.32	0.92	<10	5.74	1963	<1	0.25	254	610	34	10	<20	249	0.08	<10	143	<10	5	123
S07-34581	0.8	4.62	50	170	<5	4.26	2	23	405	73	5.40	1.82	20	2.47	1372	19	0.10	175	790	42	10	<20	202	0.08	<10	186	<10	7	212
S07-34582	2.2	5.16	25	320	<5	3.69	2	16	167	75	5.33	2.37	20	1.75	1099	33	0.10	83	950	68	15	<20	180	0.10	<10	238	<10	8	199
S07-34583	2.0	4.45	20	120	<5	3.90	2	17	169	104	5.15	2.00	20	1.75	1233	27	0.07	79	840	56	10	<20	182	0.09	<10	207	<10	7	217
S07-34584	2.4	5.34	25	200	<5	3.62	2	18	170	82	5.53	2.28	20	1.65	1089	35	0.08	85	1030	82	15	<20	168	0.11	<10	250	<10	7	228
S07-34585	1.9	4.71	20	120	<5	3.24	2	16	146	66	5.42	2.04	20	1.44	954	32	0.08	76	1000	68	10	<20	154	0.10	<10	233	<10	6	223
S07-34586	2.0	4.78	20	190	<5	3.34	3	16	191	68	5.35	2.01	20	1.50	977	34	0.07	82	1120	66	15	<20	170	0.10	<10	245	<10	7	265
S07-34587	1.8	4.96	20	185	<5	3.30	3	16	141	76	5.19	2.13	20	1.44	1032	40	0.09	79	950	56	10	<20	145	0.11	<10	253	<10	6	241
S07-34588	0.4	5.88	15	330	<5	4.38	<1	14	140	93	3.83	1.49	20	1.86	1056	9	0.80	39	800	32	<5	<20	238	0.16	<10	155	<10	9	102
S07-34589	0.4	6.61	10	315	<5	3.63	2	13	169	79	3.54	1.69	20	1.49	672	12	1.37	37	850	30	<5	<20	216	0.19	<10	253	<10	6	157
S07-34590	0.8	5.45	120	325	<5	0.26	<1	8	24	30	3.24	4.09	10	0.33	170	3	0.08	16	520	22	40	<20	56	0.39	<10	69	<10	12	45
S07-34591	0.6	6.45	15	200	<5	4.11	<1	16	164	84	4.69	1.57	20	1.59	647	9	1.39	31	690	40	<5	<20	222	0.20	<10	209	<10	8	120
S07-34592	0.4	6.90	20	200	<5	3.02	4	19	180	103	5.37	2.46	20	1.23	541	26	1.04	55	760	38	<5	<20	145	0.18	<10	465	<10	6	389
S07-34593	0.6	6.70	10	250	<5	4.61	2	17	160	104	4.53	1.55	20	1.40	760	19	1.38	47	810	32	<5	<20	224	0.17	<10	275	<10	7	205
S07-34594	0.6	7.43	15	435	<5	4.33	<1	24	164	94	5.52	2.20	20	1.57	885	13	2.04	37	860	40	<5	<20	254	0.20	<10	246	<10	8	120
S07-34595	0.8	7.18	10	215	<5	3.58	<1	17	147	73	4.44	2.27	20	1.13	622	10	1.73	32	940	44	<5	<20	189	0.17	<10	207	<10	7	102
S07-34596	0.2	6.61	5	245	<5	4.70	<1	9	126	43	3.30	1.56	20	1.58	922	8	1.34	19	1180	34	<5	<20	202	0.13	<10	102	<10	9	91
S07-34597	0.6	9.37	15	285	<5	5.83	<1	14	114	35	4.36	2.49	30	2.32	1010	2	0.76	20	1050	48	<5	<20	317	0.20	<10	128	<10	12	53
S07-34598	0.4	8.38	15	250	<5	5.73	<1	17	106	49	4.63	2.71	20	1.77	1166	1	1.69	25	870	46	<5	<20	261	0.18	<10	129	<10	8	54
S07-34599	0.2	7.60	10	385	<5	5.99	<1	13	97	48	4.11	1.77	10	2.08	1275	<1	1.54	14	1070	34	<5	<20	236	0.15	<10	116	<10	8	49
S07-34600	0.4	8.35	10	355	<5	6.06	<1	14	88	56	4.15	1.96	20	2.06	1271	<1	1.53	14	1110	42	<5	<20	233	0.16	<10	124	<10	8	56
S07-34601	0.4	7.05	10	625	<5	5.00	<1	8	136	42	3.07	1.60	20	1.87	1020	1	0.83	11	780	34	<5	<20	210	0.14	<10	87	<10	9	63
S07-34602	0.2	7.46	<5	1220	<5	3.40	<1	7	115	48	2.54	1.71	10	1.74	697	<1	0.52	11	470	30	<5	<20	237	0.16	<10	76	<10	7	39

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
S07-34603	0.8	6.90	10	1080	<5	2.95	<1	8	91	40	2.57	2.64	20	1.57	645	1	1.20	11	570	28	<5	<20	163	0.12	<10	69	<10	7	64
S07-34604	1.0	7.36	15	900	<5	3.61	<1	13	147	78	3.89	2.16	20	1.50	746	7	1.71	29	800	32	<5	<20	194	0.15	<10	186	<10	9	108
S07-34605	1.2	7.02	10	950	<5	3.93	<1	15	126	80	4.29	2.09	10	1.81	804	10	0.96	28	590	36	<5	<20	208	0.13	<10	214	<10	9	100
S07-34606	1.0	6.93	10	1125	<5	3.65	<1	7	105	52	2.69	2.15	20	1.54	921	19	0.95	13	690	28	<5	<20	164	0.15	<10	93	<10	11	61
S07-34607	0.8	3.93	5	705	<5	1.90	6	5	235	22	1.94	1.69	<10	0.85	468	11	0.37	9	330	24	<5	<20	107	0.08	<10	58	<10	6	555
S07-34608	0.6	6.53	10	1150	<5	2.59	<1	8	95	29	2.78	2.38	10	1.13	557	5	0.57	7	500	26	<5	<20	133	0.11	<10	56	<10	10	59
S07-34609	1.0	6.73	10	940	<5	3.68	<1	11	99	58	3.73	2.05	20	1.46	864	11	0.87	13	680	30	<5	<20	170	0.15	<10	132	<10	9	67
S07-34610	1.0	6.79	10	945	<5	3.62	<1	11	123	69	3.73	2.55	20	1.32	848	10	1.19	15	690	28	<5	<20	174	0.15	<10	127	<10	10	77
S07-34611	1.0	6.92	15	760	<5	3.84	<1	13	145	52	4.51	2.21	20	1.09	1174	13	1.39	18	800	28	<5	<20	174	0.17	<10	113	30	9	78
S07-34612	<0.2	0.08	<5	40	<5	>10	<1	<1	2	<1	0.04	0.01	<10	1.49	22	<1	0.02	18	40	<2	<5	<20	5901	<0.01	<10	3	<10	<1	10
S07-34613	0.8	6.97	5	1090	<5	4.27	<1	10	91	56	4.12	2.30	20	1.61	1118	<1	0.63	11	1090	32	<5	<20	213	0.17	<10	101	<10	9	76
S07-34614	0.8	5.89	10	1130	<5	3.17	<1	9	161	38	3.39	2.36	20	1.31	874	<1	0.61	10	1080	30	<5	<20	212	0.14	<10	64	<10	11	75
S07-34615	0.4	5.90	5	1185	<5	2.68	<1	5	190	33	2.69	2.57	20	1.03	646	<1	0.21	9	1710	22	<5	<20	180	0.11	<10	52	<10	14	49
S07-34616	0.6	6.56	10	1070	<5	3.23	<1	16	120	79	5.07	2.33	20	1.73	971	3	0.23	16	1230	34	<5	<20	203	0.14	<10	119	<10	9	74
S07-34617	0.2	6.32	10	1010	<5	2.44	<1	15	125	41	4.71	2.51	10	1.66	907	<1	0.99	22	730	26	<5	<20	172	0.18	<10	106	<10	8	76
S07-34618	1.2	7.13	10	1260	<5	2.68	<1	16	149	286	5.28	2.74	20	1.83	908	<1	0.70	20	1320	44	<5	<20	196	0.19	<10	128	<10	10	98
S07-34619	0.4	6.45	10	1045	<5	2.85	<1	15	132	55	4.76	2.57	10	1.58	976	<1	0.94	16	1160	32	<5	<20	207	0.17	<10	114	<10	8	94
S07-34620	0.4	7.41	20	1005	<5	5.32	<1	15	79	36	5.98	3.08	20	2.08	1739	<1	0.69	14	1470	24	<5	<20	317	0.18	<10	125	<10	8	85
S07-34621	0.4	7.01	10	1070	<5	4.14	<1	12	89	26	5.41	2.87	20	2.06	1415	<1	0.59	12	1330	28	<5	<20	280	0.18	<10	97	<10	9	69
S07-34622	0.4	7.27	15	1015	<5	3.87	<1	15	88	44	5.49	2.86	20	1.88	1346	<1	0.74	12	1280	30	<5	<20	272	0.19	<10	106	<10	9	82
S07-34623	0.6	7.49	10	950	<5	3.42	<1	15	81	47	5.51	2.83	20	1.91	1131	<1	0.54	13	1250	28	<5	<20	239	0.19	<10	104	<10	9	90
S07-34624	5.0	4.48	80	360	<5	0.46	2	11	36	614	5.20	2.50	10	1.67	370	7	0.23	23	500	96	50	<20	72	0.27	<10	51	<10	10	658
S07-34625	0.4	6.89	10	925	<5	3.24	<1	14	89	45	5.13	2.77	20	1.86	1064	<1	0.55	12	1170	30	<5	<20	236	0.20	<10	101	<10	9	80
S07-34626	0.4	7.32	15	990	<5	3.01	<1	15	105	59	5.75	2.92	20	1.84	971	<1	0.80	14	1290	28	<5	<20	274	0.22	<10	101	<10	11	84
S07-34627	0.2	7.46	15	820	<5	4.05	<1	14	121	57	4.63	2.62	20	1.45	1096	3	1.39	16	850	26	<5	<20	343	0.19	<10	126	<10	8	74
S07-34628	1.8	6.83	15	850	<5	2.67	<1	9	116	58	3.69	2.38	20	0.88	757	10	1.69	13	640	28	<5	<20	250	0.17	<10	96	<10	11	75
S07-34629	0.6	7.60	15	1210	<5	3.18	<1	7	66	52	3.48	2.73	30	1.05	890	12	1.32	7	870	28	<5	<20	303	0.17	<10	57	<10	14	58
S07-34630	0.6	7.78	10	895	<5	3.07	<1	10	110	56	4.08	2.88	20	1.46	995	7	1.63	12	1290	28	<5	<20	328	0.18	<10	114	<10	11	68
S07-34631	0.6	7.64	20	690	<5	2.82	<1	14	97	57	4.31	2.36	20	1.54	976	<1	2.28	17	1120	32	<5	<20	286	0.18	<10	138	<10	8	68
S07-34632	0.8	6.26	35	575	<5	2.58	<1	19	208	100	4.55	2.00	10	1.26	945	<1	1.80	35	590	28	<5	<20	223	0.15	<10	144	<10	5	92
S07-34633	0.6	7.20	15	585	<5	2.73	<1	18	144	67	4.96	2.17	10	1.80	1163	<1	2.19	26	680	30	<5	<20	265	0.17	<10	157	<10	6	86
S07-34634	0.6	7.58	15	505	<5	4.89	<1	16	101	94	4.76	2.13	<10	1.95	1635	<1	2.69	21	960	28	<5	<20	378	0.17	<10	170	<10	6	61
S07-34635	0.6	7.51	10	400	<5	2.92	<1	15	94	56	4.26	1.61	10	1.66	1190	<1	3.16	21	610	26	<5	<20	287	0.19	<10	123	<10	8	72
S07-34636	0.8	7.61	20	410	<5	3.17	<1	17	140	69	4.87	1.76	10	1.82	1281	<1	3.00	25	630	30	<5	<20	294	0.19	<10	135	<10	7	80
S07-34637	0.4	7.62	20	550	<5	3.18	<1	18	122	38	4.74	2.67	10	1.84	1393	<1	1.30	24	680	28	<5	<20	258	0.19	<10	162	<10	7	65
S07-34638	0.6	7.95	25	480	<5	2.74	<1	18	97	60	5.42	2.17	10	1.92	1343	<1	2.39	34	810	32	<5	<20	263	0.21	<10	183	<10	6	95
S07-34639	0.8	6.92	25	450	<5	2.74	<1	20	144	159	4.89	1.81	10	1.62	1374	<1	2.71	82	560	30	<5	<20	271	0.17	<10	170	<10	4	84
S07-34640	0.8	7.92	25	470	<5	2.98	<1	20	87	59	5.83	2.21	10	2.18	1561	<1	2.89	42	760	30	<5	<20	299	0.18	<10	193	<10	5	112
S07-34641	0.8	7.18	20	340	<5	2.89	<1	15	108	111	3.90	1.42	10	1.43	1324	<1	3.77	28	710	28	<5	<20	298	0.18	<10	141	<10	5	67
S07-34642	0.2	7.18	15	400	<5	2.64	<1	17	117	65	4.51	1.96	10	1.55	1198	<1	2.59	26	820	30	<5	<20	240	0.19	<10	133	<10	6	60

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
S07-34643	0.6	6.88	20	475	<5	3.29	<1	21	133	60	4.97	2.14	10	1.67	1367	<1	2.15	30	650	30	<5	<20	264	0.17	<10	138	<10	6	61
S07-34644	0.8	6.90	20	655	<5	4.62	<1	18	183	68	5.43	2.83	10	1.78	1554	<1	0.80	29	840	54	<5	<20	303	0.16	<10	183	<10	6	88
S07-34645	1.2	6.54	25	495	<5	3.54	<1	26	142	128	6.18	2.81	10	1.88	1320	<1	0.33	33	780	50	<5	<20	267	0.14	<10	192	<10	5	64
S07-34646	0.6	8.15	15	760	<5	3.98	<1	20	112	77	5.96	3.09	10	2.24	1755	<1	1.24	24	860	46	<5	<20	260	0.21	<10	197	<10	6	88
S07-34647	0.8	8.22	15	720	<5	3.66	<1	21	131	79	5.74	2.98	<10	2.29	1610	<1	1.73	22	790	42	<5	<20	260	0.21	<10	206	<10	5	115
S07-34648	<0.2	0.11	<5	15	<5	>10	<1	<1	2	2	0.06	0.01	<10	1.53	24	<1	0.02	23	40	<2	<5	<20	5802	<0.01	<10	2	<10	<1	7
S07-34649	0.4	8.04	15	725	<5	4.13	<1	19	66	107	5.62	2.70	<10	1.94	1460	<1	1.93	23	710	38	<5	<20	277	0.21	<10	197	<10	6	75
S07-34650	0.4	6.88	15	660	<5	4.10	<1	18	94	69	5.08	2.51	10	1.96	1204	<1	1.72	20	730	28	<5	<20	301	0.17	<10	185	<10	6	77
S07-34651	0.4	7.30	10	585	<5	2.75	<1	16	97	86	5.05	2.18	10	1.85	1081	<1	2.42	25	580	30	<5	<20	248	0.19	<10	167	<10	5	81
S07-34652	1.2	6.91	15	640	<5	3.18	<1	16	122	25	4.98	2.54	<10	1.97	1327	<1	1.54	22	520	28	<5	<20	258	0.16	<10	165	<10	4	87
S07-34653	0.4	6.75	15	555	<5	2.75	<1	16	120	50	4.53	2.08	10	1.59	1136	<1	2.07	31	570	24	<5	<20	233	0.18	<10	133	<10	6	57
S07-34654	0.4	7.43	15	710	<5	3.49	<1	17	119	95	5.32	2.76	10	1.92	1401	<1	1.26	23	750	38	<5	<20	260	0.20	<10	187	<10	6	60
S07-34655	0.4	7.79	25	615	<5	4.04	<1	22	101	81	5.76	2.54	10	1.86	1489	<1	1.80	27	740	38	<5	<20	266	0.20	<10	175	<10	5	70
S07-34656	0.4	7.90	15	635	<5	3.19	<1	16	74	82	4.59	2.25	10	1.69	1086	<1	2.23	20	700	32	<5	<20	244	0.18	<10	145	<10	6	76
S07-34657	0.4	8.48	15	515	<5	3.40	<1	16	56	75	4.52	2.54	10	1.59	1048	<1	2.15	15	940	28	<5	<20	244	0.19	<10	128	<10	5	81
S07-34658	0.4	7.99	20	580	<5	4.07	<1	21	49	67	5.57	2.67	10	1.79	1284	<1	2.01	22	860	30	<5	<20	264	0.21	<10	149	<10	6	87
S07-34659	0.6	7.02	10	495	<5	2.83	<1	11	37	86	4.04	2.37	10	1.35	905	<1	2.04	11	800	36	<5	<20	207	0.16	<10	95	<10	4	115
S07-34660	6.0	3.91	125	360	<5	0.35	<1	7	41	49	3.31	2.87	<10	0.24	224	6	0.49	20	400	20	65	<20	99	0.28	<10	49	<10	10	48
S07-34661	<0.2	7.71	15	520	<5	3.50	<1	15	59	94	4.57	2.47	10	1.56	1006	<1	1.96	17	820	26	<5	<20	247	0.19	<10	128	<10	5	78
S07-34662	0.6	8.11	30	615	<5	3.62	<1	17	80	73	5.15	2.32	10	1.79	1073	<1	2.02	22	830	28	<5	<20	356	0.18	<10	163	<10	5	60
S07-34663	0.4	7.36	25	560	<5	5.57	<1	24	88	79	6.17	2.12	<10	2.33	1477	<1	1.88	28	820	36	<5	<20	400	0.22	<10	217	<10	5	77
S07-34664	0.2	8.51	30	765	<5	3.49	<1	19	74	92	5.63	2.71	<10	1.79	1042	<1	1.98	23	870	34	<5	<20	267	0.20	<10	179	<10	5	90
S07-34665	0.6	7.98	25	760	<5	3.22	<1	17	81	93	5.39	2.74	10	1.81	992	<1	2.13	21	810	36	<5	<20	277	0.19	<10	179	<10	5	70
S07-34666	0.4	6.49	15	550	<5	3.09	<1	12	137	84	3.98	2.45	10	1.30	992	<1	1.16	15	950	20	<5	<20	227	0.17	<10	100	<10	5	63
S07-34667	0.6	7.62	10	575	<5	3.34	<1	15	62	69	4.53	2.46	10	1.54	984	<1	2.15	18	790	24	<5	<20	252	0.18	<10	127	<10	5	62
S07-34668	0.4	8.01	25	720	<5	3.65	<1	17	83	61	5.33	2.85	10	1.94	1079	<1	1.69	21	1000	32	<5	<20	284	0.20	<10	175	<10	5	52
S07-34669	0.6	8.70	15	880	<5	4.98	<1	21	75	72	5.63	3.67	10	2.20	1485	<1	1.06	22	1240	42	<5	<20	349	0.22	<10	220	<10	6	38
S07-34670	1.2	8.41	20	865	<5	4.66	<1	21	90	71	5.67	3.58	10	2.17	1458	<1	1.03	25	1140	48	<5	<20	351	0.18	<10	209	<10	6	40
S07-34671	0.4	7.99	10	685	<5	3.84	5	19	84	59	5.33	3.30	<10	2.14	1187	<1	1.12	19	790	462	<5	<20	284	0.19	<10	191	<10	4	466
S07-34672	0.2	7.53	10	880	<5	3.58	<1	9	72	37	3.31	3.09	20	1.14	704	<1	0.80	11	660	24	<5	<20	258	0.17	<10	96	<10	7	58
S07-34673	0.4	7.02	15	715	<5	3.30	<1	12	85	29	3.16	2.82	20	0.86	601	<1	1.01	12	650	26	<5	<20	267	0.15	<10	62	<10	6	41
S07-34674	1.2	8.26	20	830	<5	5.69	<1	19	103	47	4.92	3.15	10	2.10	1331	<1	0.88	25	1050	36	<5	<20	506	0.22	<10	176	<10	7	45
S07-34675	1.2	8.15	25	660	<5	5.90	<1	21	68	236	7.36	3.13	20	2.47	1385	61	0.86	15	2020	58	<5	<20	407	0.29	<10	236	<10	12	87
S07-34676	1.2	7.95	20	530	<5	5.43	<1	22	65	288	7.79	2.80	20	2.49	1357	30	0.88	13	2110	46	<5	<20	327	0.32	<10	242	<10	11	93
S07-34677	1.8	8.72	25	590	<5	6.36	<1	17	84	333	7.34	3.03	20	2.51	1559	30	1.51	13	2190	60	<5	<20	474	0.36	<10	261	<10	12	111
S07-34678	0.4	8.39	20	555	<5	5.95	<1	18	116	351	7.74	2.91	20	2.82	1885	74	0.59	14	2450	60	<5	<20	538	0.40	<10	259	<10	14	92
S07-34679	0.4	6.34	15	345	<5	4.10	<1	15	133	132	6.81	1.63	20	2.53	1568	3	0.49	14	1790	28	<5	<20	281	0.32	<10	180	<10	12	55
S07-34680	0.8	6.81	20	585	<5	4.17	<1	13	151	43	4.36	1.93	10	1.96	1137	<1	0.56	17	950	40	<5	<20	297	0.23	<10	136	<10	8	57

VIA:

ref:

S07-34497	1.0	4.34	50	705	<5	0.48	<1	19	153	103	3.72	0.91	20	0.26	1957	1	1.60	40	380	26	<5	<20	67	0.11	<10	42	<10	7	69
-----------	-----	------	----	-----	----	------	----	----	-----	-----	------	------	----	------	------	---	------	----	-----	----	----	-----	----	------	-----	----	-----	---	----

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La ...%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
S07-34516	0.6	3.99	90	695	<5	3.17	<1	33	464	8	4.46	0.86	10	4.34	2257	<1	0.15	264	600	70	10	<20	264	0.06	<10	117	<10	5	56
S07-34533	0.5	4.48	50	660	<5	3.81	<1	29	571	30	4.00	1.28	10	5.76	1303	<1	0.24	260	450	28	10	<20	238	0.10	<10	64	<10	8	66
S07-34542	0.4	4.41	35	80	<5	4.86	<1	43	831	39	5.53	1.09	<10	7.63	1571	<1	0.48	426	600	18	10	<20	248	0.05	<10	112	<10	6	59
S07-34551	0.4	6.09	5	1155	<5	1.12	<1	5	59	6	1.57	1.59	20	1.48	939	<1	0.46	10	330	24	<5	<20	90	0.13	<10	26	<10	8	35
S07-34568	0.4	4.05	80	30	<5	7.35	<1	44	644	23	5.74	0.38	<10	9.34	1915	<1	0.51	431	660	20	10	<20	341	0.05	<10	111	<10	7	73
S07-34577	0.4	5.77	25	335	<5	3.98	<1	20	352	114	4.44	1.25	20	3.48	1330	17	0.15	136	830	42	5	<20	239	0.11	<10	183	<10	9	83
S07-34586	1.7	4.59	15	205	<5	3.50	3	15	198	68	5.14	2.07	20	1.47	930	32	0.08	76	1050	64	15	<20	164	0.09	<10	243	<10	7	257
S07-34603	0.8	6.96	5	1115	<5	2.83	<1	8	100	41	2.58	2.52	20	1.64	629	1	1.26	10	560	28	<5	<20	170	0.10	<10	69	<10	7	70
S07-34613	1.0	7.09	5	1100	<5	4.40	<1	10	94	59	4.13	2.22	20	1.64	1123	1	0.65	12	1100	32	<5	<20	214	0.16	<10	103	<10	11	80
S07-34621	0.5	6.71	10	1065	<5	3.92	<1	12	89	26	5.05	2.86	20	2.05	1392	<1	0.60	11	1260	26	<5	<20	280	0.17	<10	99	<10	9	65
S07-34638	0.6	7.80	20	490	<5	2.59	<1	18	101	65	5.38	2.21	10	1.97	1302	<1	2.49	33	780	32	<5	<20	268	0.19	<10	184	<10	6	90
S07-34647	1.0	8.19	15	720	<5	3.76	<1	21	133	82	5.69	3.01	10	2.31	1592	<1	1.74	21	770	40	<5	<20	261	0.20	<10	208	<10	5	119
S07-34656	0.4	8.02	20	645	<5	2.96	<1	14	85	86	4.78	2.29	10	1.72	1126	<1	2.40	21	730	32	<5	<20	247	0.19	<10	147	<10	5	71
S07-34673	0.6	7.05	15	705	<5	3.31	<1	13	87	29	3.16	2.76	20	0.85	596	<1	0.99	13	640	28	<5	<20	266	0.15	<10	61	<10	6	45

it:

S07-34497	0.8	4.84	45	805	<5	0.49	<1	19	166	90	3.63	1.06	20	0.29	1996	<1	1.76	37	390	28	<5	<20	72	0.13	<10	45	<10	9	67
S07-34533	0.7	4.71	50	725	<5	3.76	<1	27	555	34	4.03	1.05	20	5.62	1332	<1	0.27	256	460	30	10	<20	238	0.11	<10	65	<10	8	67
S07-34568	0.2	4.12	65	30	<5	7.18	<1	43	674	24	5.64	0.44	<10	9.21	1866	<1	0.50	436	670	22	10	<20	333	0.05	<10	114	<10	7	78
S07-34603	0.8	6.77	10	1030	<5	2.84	<1	8	98	38	2.62	2.51	20	1.53	608	2	1.30	12	520	24	<5	<20	163	0.10	<10	69	<10	8	59
S07-34638	0.6	7.97	20	475	<5	2.83	<1	18	93	70	5.23	2.24	10	1.88	1326	<1	2.56	33	790	30	<5	<20	277	0.19	<10	180	<10	5	86
S07-34673	0.6	6.92	10	695	<5	3.46	<1	9	83	31	2.98	2.67	20	0.80	593	<1	1.04	10	560	24	<5	<20	256	0.16	<10	57	<10	8	41

ard:


0.5	5.96	30	1300	<5	2.41	<1	15	61	37	4.16	1.27	30	1.32	2609	5	1.12	34	1760	50	<5	<20	262	0.34	<10	104	<10	29	198
0.4	5.74	30	1280	<5	2.47	<1	16	63	36	4.21	1.26	30	1.32	2549	5	1.12	35	1790	58	5	<20	284	0.36	<10	119	<10	28	206
0.5	5.73	25	1305	<5	2.50	<1	16	62	36	4.21	1.31	30	1.34	2574	6	1.13	35	1710	52	<5	<20	274	0.36	<10	110	<10	29	204
0.4	5.32	25	1395	<5	2.31	<1	14	55	35	4.15	1.31	30	1.29	2452	5	1.13	31	1760	56	<5	<20	267	0.31	<10	101	<10	28	194
0.4	5.80	25	1240	<5	2.30	<1	15	56	36	4.19	1.27	30	1.34	2502	5	1.11	32	1810	56	<5	<20	279	0.33	<10	102	<10	27	199
0.4	5.62	25	1215	<5	2.33	<1	15	55	35	4.22	1.31	30	1.31	2597	4	1.19	31	1730	56	<5	<20	282	0.32	<10	106	<10	27	193


1 ACID DIGEST/ICP-FINISH

4 ACID DIGEST/AA-FINISH

0as/td2290bs

7


ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2289

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

10-Mar-08


Attention: Bob Singh

No. of samples received: 58
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-156
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #		Au (g/t)	Au (oz/t)
1	S07-34681	*	<0.03	<0.001
2	S07-34682		0.09	0.002
3	S07-34683		0.10	0.003
4	S07-34684		<0.03	<0.001
5	S07-34685		<0.03	<0.001
6	S07-34686		0.65	0.019
7	S07-34687		0.13	0.004
8	S07-34688		0.10	0.003
9	S07-34689		0.29	0.009
10	S07-34690		<0.03	<0.001
11	S07-34691		<0.03	<0.001
12	S07-34692		<0.03	<0.001
13	S07-34693	*	0.42	0.012
14	S07-34694		<0.03	<0.001
15	S07-34695		0.11	0.003
16	S07-34696		0.06	0.002
17	S07-34697		<0.03	<0.001
18	S07-34698		<0.03	<0.001
19	S07-34699		0.05	0.002
20	S07-34700		0.03	0.001
21	S07-34701		0.11	0.003
22	S07-34702		0.03	0.001
23	S07-34703		0.04	0.001
24	S07-34704		0.09	0.003
25	S07-34705		0.13	0.004
26	S07-34706		0.17	0.005
27	S07-34707		0.05	0.001
28	S07-34708		0.07	0.002

* = 30g FA



Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	S07-34709	0.08	0.002
30	S07-34710	<0.03	<0.001
31	S07-34711	<0.03	<0.001
32	S07-34712	0.07	0.002
33	S07-34713	<0.03	<0.001
34	S07-34714	0.07	0.002
35	S07-34715	<0.03	<0.001
36	S07-34716	<0.03	<0.001
37	S07-34717	0.04	0.001
38	S07-34718	* <0.03	<0.001
39	S07-34719	0.05	0.002
40	S07-34720	0.04	0.001
41	S07-34721	0.05	0.001
42	S07-34722	0.09	0.003
43	S07-34723	0.19	0.006
44	S07-34724	0.04	0.001
45	S07-34725	0.08	0.002
46	S07-34726	0.05	0.001
47	S07-34727	0.03	0.001
48	S07-34728	* 2.00	0.058
49	S07-34729	<0.03	<0.001
50	S07-34730	0.16	0.005
51	S07-34731	<0.03	<0.001
52	S07-34732	0.04	0.001
53	S07-34733	0.09	0.002
54	S07-34734	0.03	0.001
55	S07-34735	0.06	0.002
56	S07-34736	0.04	0.001
57	S07-34737	0.07	0.002
58	S07-34738	<0.03	<0.001

QC DATA:

Standard:

OXI54	1.90	0.055
OXI54	1.87	0.055
OXI54	1.90	0.055
OXI54	1.84	0.054
OXI54	1.82	0.053

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

U/nw
LS/07



ECO TECH LABORATORY LTD.

Jutta Jealous
B.C. Certified Assayer

TECH LABS. LAB. LTD.
 1 Dallas Drive
 ILLOOPS, B.C.
 6T4

ICP CERTIFICATE OF ANALYSIS K 2007-2289

Skygold Ventures
 615 - 800 W. Pender Street
 Vancouver, BC
 V6B 2V6

Phone: 250-573-5700
 Fax: 250-573-4557

No. of samples received: 58
 Sample Type: Core
 Project: Spanish Mountain
 Shipment #: SMC-07-156
 Samples submitted by: Tasha Gainer

Concentrations in ppm unless otherwise reported


#.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
	S07-34681	<0.2	0.07	<5	15	<5	>10	<1	<1	3	3	0.53	0.03	<10	>10	200	<1	0.02	2	200	<2	<5	<20	57	<0.01	<10	2	<10	<1	13
	S07-34682	0.3	7.57	15	575	<5	4.20	<1	12	73	42	4.30	2.44	10	1.59	1160	<1	1.73	13	940	28	<5	<20	321	0.22	<10	137	<10	7	68
	S07-34683	0.4	7.88	20	815	<5	3.63	<1	8	59	42	3.70	3.05	10	1.42	920	<1	0.52	10	760	26	<5	<20	298	0.17	<10	66	<10	5	51
	S07-34684	0.2	7.61	10	695	<5	4.46	<1	11	152	60	4.05	2.69	10	1.85	1166	<1	0.52	12	750	30	<5	<20	393	0.23	<10	102	<10	14	58
	S07-34685	<0.2	7.69	5	700	<5	3.78	<1	8	93	54	3.54	2.55	20	1.58	890	<1	1.16	10	670	28	<5	<20	388	0.19	<10	81	<10	12	40
	S07-34686	0.2	7.02	30	595	<5	3.64	<1	22	151	39	5.69	2.74	<10	1.73	1014	<1	0.30	22	690	32	<5	<20	364	0.19	<10	130	<10	9	49
	S07-34687	0.2	7.81	15	865	<5	2.72	<1	14	148	56	5.02	2.47	<10	2.10	957	<1	0.91	16	770	32	<5	<20	370	0.24	<10	156	<10	8	59
	S07-34688	0.4	8.86	15	825	<5	3.63	<1	21	49	83	5.42	2.66	<10	2.22	1035	<1	1.60	18	820	32	<5	<20	441	0.21	<10	192	<10	6	84
	S07-34689	0.4	8.59	25	705	<5	3.62	<1	15	137	30	4.56	2.86	10	2.24	1089	<1	1.25	23	960	34	<5	<20	411	0.28	<10	162	<10	9	53
	S07-34690	0.2	8.88	25	1500	<5	5.42	<1	30	120	74	7.04	3.18	<10	3.42	1316	<1	0.40	43	960	30	<5	<20	541	0.26	<10	257	<10	8	75
	S07-34691	0.2	8.20	25	700	<5	3.52	<1	20	60	98	5.74	1.91	20	2.60	975	<1	3.04	26	1400	32	<5	<20	547	0.30	<10	212	<10	10	70
	S07-34692	1.2	8.03	20	810	<5	5.22	<1	20	102	167	5.39	1.63	20	2.32	1035	3	4.15	36	1520	80	<5	<20	704	0.24	<10	234	<10	11	82
	S07-34693	0.8	5.86	95	415	<5	0.23	<1	8	23	32	3.22	4.44	10	0.30	171	3	0.11	15	520	22	40	<20	53	0.37	<10	68	<10	12	45
	S07-34694	0.4	7.70	35	760	<5	4.28	<1	27	170	29	6.34	2.54	10	3.36	1049	<1	1.39	66	1240	32	<5	<20	439	0.18	<10	258	<10	8	67
	S07-34695	0.6	7.67	35	530	<5	4.17	<1	27	169	119	6.29	2.44	10	3.53	1049	<1	1.53	70	1360	54	<5	<20	415	0.20	<10	255	<10	10	73
	S07-34696	0.6	7.14	40	610	<5	4.44	<1	29	246	181	6.62	2.06	10	4.17	1145	<1	0.55	89	1150	44	<5	<20	423	0.18	<10	248	<10	9	65
	S07-34697	0.4	8.35	25	1420	<5	3.86	<1	27	86	90	6.03	1.89	10	3.38	1032	<1	2.27	40	1580	30	<5	<20	466	0.23	<10	220	<10	11	72
	S07-34698	0.4	8.40	25	1645	<5	3.63	<1	25	73	95	5.95	1.94	10	2.92	1137	<1	3.42	35	1160	32	<5	<20	455	0.24	<10	226	<10	10	65
	S07-34699	0.9	7.99	15	1205	<5	3.29	<1	23	68	84	5.81	2.01	10	2.90	1041	<1	3.32	35	1100	32	<5	<20	411	0.21	<10	208	<10	9	57
	S07-34700	0.6	8.29	15	1470	<5	3.36	<1	26	55	103	5.70	2.21	10	2.78	1172	<1	3.52	31	1140	32	<5	<20	384	0.24	<10	207	<10	9	69
	S07-34701	0.6	7.95	20	1630	<5	6.01	<1	20	88	91	5.60	2.02	10	2.84	1433	<1	2.90	30	1300	34	<5	<20	581	0.23	<10	192	<10	11	58
	S07-34702	0.6	7.77	25	2290	<5	3.80	<1	20	137	87	5.66	2.39	10	3.36	1348	<1	2.07	41	1170	30	<5	<20	438	0.25	<10	194	<10	11	64
	S07-34703	0.4	7.27	20	2220	<5	5.07	<1	27	207	88	6.17	2.48	10	3.86	1798	<1	1.85	68	1210	34	<5	<20	465	0.20	<10	218	<10	9	58
	S07-34704	0.4	7.26	30	2875	<5	4.86	<1	29	292	91	6.30	2.95	10	4.28	1796	<1	0.98	89	1140	30	<5	<20	462	0.19	<10	223	<10	9	70
	S07-34705	0.2	5.43	25	1610	<5	2.58	<1	17	340	36	4.74	2.05	<10	2.39	1093	<1	0.63	49	790	24	5	<20	280	0.17	<10	126	<10	8	54

#.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Li mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	V	W	Y	Zn		
5	S07-34706	0.2	8.34	10	1575	<5	2.08	<1	14	78	50	5.04	2.13	20	2.49	1060	<1	3.13	16	1250	38	<5	<20	347	0.22	<10	123	<10	8	53
7	S07-34707	0.4	7.91	15	1800	<5	2.33	<1	18	79	66	5.93	2.16	10	2.35	1281	<1	2.80	22	1400	36	<5	<20	337	0.23	<10	152	<10	8	72
3	S07-34708	0.4	8.00	10	3330	<5	2.18	<1	14	80	55	5.69	2.28	10	2.50	1252	<1	2.78	18	1280	36	<5	<20	323	0.25	<10	162	<10	10	73
3	S07-34709	0.2	7.15	20	940	<5	1.53	<1	10	83	47	3.84	1.62	20	1.45	901	<1	3.15	11	920	32	<5	<20	292	0.17	<10	73	<10	8	49
0	S07-34710	0.2	9.35	15	3335	<5	2.03	<1	11	94	53	6.11	2.83	20	2.83	1256	<1	2.10	16	1330	38	<5	<20	299	0.24	<10	163	<10	7	72
1	S07-34711	0.6	6.52	25	2420	<5	4.83	<1	21	148	60	4.51	2.47	10	2.92	1637	<1	1.28	44	1070	26	<5	<20	565	0.25	<10	177	<10	9	45
2	S07-34712	0.6	7.10	25	1925	<5	4.33	<1	27	191	43	6.04	2.90	<10	3.63	1677	<1	0.84	64	1320	32	<5	<20	509	0.21	<10	210	<10	8	55
3	S07-34713	0.4	6.57	10	1860	<5	2.16	<1	16	233	36	5.16	2.71	<10	2.59	1221	<1	0.76	27	1020	26	<5	<20	288	0.18	<10	181	<10	7	55
4	S07-34714	0.2	8.23	20	2100	<5	2.34	<1	24	98	86	6.05	2.47	10	3.07	1346	<1	2.48	31	1210	38	<5	<20	351	0.24	<10	214	<10	8	72
5	S07-34715	0.6	7.64	15	1000	<5	2.53	<1	16	67	83	5.44	1.49	20	2.92	1342	<1	3.92	24	1300	32	<5	<20	377	0.20	<10	134	<10	12	75
6	S07-34716	0.6	7.82	20	2100	<5	1.92	<1	23	99	83	6.08	2.65	10	3.45	1366	<1	2.45	36	1150	30	<5	<20	268	0.19	<10	224	<10	5	81
7	S07-34717	0.8	7.37	20	2195	<5	3.95	<1	25	108	65	6.12	2.78	10	3.72	1818	<1	1.54	44	1050	28	<5	<20	419	0.18	<10	215	<10	8	81
3	S07-34718	0.2	0.13	<5	20	<5	>10	<1	<1	1	<1	0.53	0.04	<10	>10	188	<1	0.05	2	200	4	<5	<20	56	<0.01	<10	4	<10	<1	13
3	S07-34719	0.6	7.14	20	2555	<5	2.95	<1	18	77	35	5.21	2.31	10	2.86	1174	6	0.86	29	850	28	<5	<20	334	0.17	<10	173	<10	6	81
0	S07-34720	0.4	6.86	15	2675	<5	1.41	<1	17	82	101	5.13	3.47	10	2.53	815	4	0.21	35	780	28	<5	<20	177	0.17	<10	194	<10	6	114
1	S07-34721	0.4	7.07	20	2495	<5	1.37	<1	12	89	79	4.30	3.04	10	2.17	884	2	0.17	47	520	28	<5	<20	167	0.17	<10	139	<10	8	99
2	S07-34722	0.6	6.28	20	2110	<5	1.67	<1	13	89	130	3.84	3.15	10	1.88	1097	<1	0.14	42	550	28	<5	<20	181	0.16	<10	144	<10	7	111
3	S07-34723	0.8	6.52	15	2060	<5	1.78	<1	13	89	96	3.61	3.02	10	1.70	1195	1	0.14	41	480	26	<5	<20	188	0.18	<10	191	<10	6	120
4	S07-34724	0.2	5.46	15	1705	<5	1.59	2	12	133	76	3.74	2.82	20	1.75	1217	5	0.12	75	520	26	<5	<20	175	0.15	<10	167	<10	6	262
5	S07-34725	0.8	4.70	25	1365	<5	1.73	1	11	178	80	3.12	2.59	10	1.41	1712	5	0.14	113	460	20	<5	<20	246	0.14	<10	106	<10	6	182
6	S07-34726	0.6	5.79	25	1555	<5	2.32	1	14	135	84	3.58	2.83	20	1.69	2414	4	0.13	115	770	22	<5	<20	243	0.18	<10	109	<10	7	206
7	S07-34727	1.0	6.38	30	1840	<5	1.90	<1	14	116	79	3.70	2.47	20	1.86	1958	5	0.15	114	580	30	<5	<20	215	0.19	<10	142	<10	7	152
3	S07-34728	4.9	4.48	85	310	<5	0.46	2	11	38	639	5.22	2.76	10	1.76	392	7	0.27	24	530	106	50	<20	72	0.28	<10	56	<10	11	676
0	S07-34729	0.8	4.87	30	1400	<5	1.88	<1	10	149	127	2.93	2.63	20	1.45	1994	4	0.09	116	370	20	<5	<20	219	0.14	<10	101	<10	5	151
0	S07-34730	0.8	6.21	25	825	<5	1.54	<1	17	176	78	4.13	3.27	30	1.55	2346	4	0.14	84	490	32	<5	<20	188	0.17	<10	100	<10	5	117
1	S07-34731	0.4	7.13	30	1700	<5	1.35	<1	12	146	77	3.30	3.26	30	1.61	2786	<1	0.18	87	590	32	<5	<20	161	0.23	<10	107	<10	6	132
2	S07-34732	0.8	4.63	35	1120	<5	1.68	<1	15	142	72	3.38	2.42	20	1.64	3887	<1	0.11	102	420	26	<5	<20	190	0.16	<10	78	<10	5	106
3	S07-34733	1.2	7.04	60	1695	<5	1.08	<1	22	144	239	3.96	3.36	30	1.83	3711	2	0.17	232	490	32	<5	<20	135	0.23	<10	123	<10	7	192
4	S07-34734	1.2	5.74	55	1375	<5	0.94	1	20	138	202	3.75	2.99	20	1.64	3822	2	0.15	214	430	34	<5	<20	122	0.19	<10	103	<10	6	230
5	S07-34735	1.0	6.31	35	1520	<5	1.10	<1	15	130	146	3.70	3.26	30	1.76	4077	<1	0.24	128	470	32	<5	<20	143	0.19	<10	97	<10	6	143
6	S07-34736	1.0	5.06	55	1065	<5	1.70	<1	17	167	107	3.89	2.61	20	1.85	4470	<1	0.14	142	420	32	<5	<20	207	0.16	<10	87	<10	6	119
7	S07-34737	0.8	5.43	45	995	<5	1.85	<1	15	184	89	3.86	2.65	20	2.00	3808	<1	0.15	145	480	38	<5	<20	234	0.16	<10	92	<10	6	150
8	S07-34738	1.2	5.89	45	1205	<5	0.75	<1	18	178	116	3.25	2.56	30	1.60	2035	<1	0.18	153	490	32	<5	<20	115	0.22	<10	94	<10	6	129
DATA:																														
at:																														
	S07-34682	0.2	7.53	10	570	<5	4.08	<1	12	72	42	4.16	2.39	10	1.57	1124	<1	1.70	13	900	28	<5	<20	313	0.23	<10	135	<10	9	68
	S07-34690	0.3	8.27	30	1435	<5	5.35	<1	26	119	65	6.59	3.06	10	3.27	1234	<1	0.41	38	910	32	<5	<20	521	0.24	<10	251	<10	7	77
	S07-34699	0.7	8.17	20	1225	<5	3.27	<1	22	66	86	5.98	2.05	10	2.95	1071	<1	3.44	35	1140	28	<5	<20	416	0.22	<10	212	<10	9	63
	S07-34708	0.4	8.06	15	3400	<5	1.99	<1	16	84	56	5.78	2.32	20	2.53	1275	<1	2.87	19	1300	38	<5	<20	327	0.26	<10	163	<10	12	72
	S07-34716	0.6	7.87	20	2130	<5	1.95	<1	23	100	82	6.01	2.71	10	3.50	1359	<1	2.37	36	1120	30	<5	<20	274	0.19	<10	223	<10	5	74
	S07-34725	0.8	4.93	30	1295	<5	2.01	1	11	177	79	3.22	2.55	20	1.42	1765	5	0.14	120	490	23	<5	<20	245	0.15	<10	104	<10	6	185
	S07-34734	1.2	5.74	60	1410	<5	0.97	1	21	142	207	3.74	2.52	20	1.67	3791	2	0.17	226	430	34	<5	<20	123	0.19	<10	107	<10	7	222


#.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
Standard:		0.5	5.57	30	1240	<5	2.45	<1	15	58	35	4.32	1.48	30	1.35	2488	5	1.23	32	1780	58	<5	<20	270	0.32	<10	104	<10	27	195
		0.4	5.86	30	1315	<5	2.42	<1	15	59	36	4.23	1.40	40	1.33	2534	5	1.21	33	1740	58	<5	<20	265	0.33	<10	115	<10	29	202

4 ACID DIGEST/ICP-FINISH
 4 ACID DIGEST/AA-FINISH

99s
 07



TECH LABORATORY LTD.
 Jutta Jeelouse
 B.C. Certified Assayer



**ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.**

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2294

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

20-Mar-08


Attention: Bob Singh

No. of samples received: 173
Sample Type: Core
Project: **Spanish Mountain**
Shipment #: **SMC-07-157**
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-05703	<0.03	<0.001
2	S07-05704	<0.03	<0.001
3	S07-05705	<0.03	<0.001
4	S07-05706	<0.03	<0.001
5	S07-05707	<0.03	<0.001
6	S07-05708	<0.03	<0.001
7	S07-05709	<0.03	<0.001
8	S07-05710	<0.03	<0.001
9	S07-05711	<0.03	<0.001
10	S07-05712	<0.03	<0.001
11	S07-05713	0.03	0.001
12	S07-05714	0.07	0.002
13	S07-05715	0.29	0.008
14	S07-05716	0.06	0.002
15	S07-05717	0.27	0.008
16	S07-05718	0.09	0.003
17	S07-05719	0.17	0.005
18	S07-05720	0.21	0.006
19	S07-05721	0.14	0.004
20	S07-05722	<0.03	<0.001
21	S07-05723	0.17	0.005
22	S07-05724	0.25*	0.007
23	S07-05725	0.24	0.007
24	S07-05726	0.26	0.008
25	S07-05727	0.23	0.007
26	S07-05728	0.22	0.006
27	S07-05729	0.17	0.005
28	S07-05730	0.16	0.005


* = 30g FA


ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	S07-05731	0.11	0.003
30	S07-05732	<0.03	<0.001
31	S07-05733	<0.03	<0.001
32	S07-05734	6.67	0.195
33	S07-05735	<0.03	<0.001
34	S07-05736	<0.03	<0.001
35	S07-05737	0.22	0.007
36	S07-05738	0.26	0.008
37	S07-05739	0.16	0.005
38	S07-05740	0.11	0.003
39	S07-05741	0.08	0.002
40	S07-05742	1.16	0.034
41	S07-05743	0.35	0.010
42	S07-05744	0.23	0.007
43	S07-05745	0.62	0.018
44	S07-05746	0.23	0.007
45	S07-05747	0.88	0.026
46	S07-05748	0.70	0.021
47	S07-05749	1.65	0.048
48	S07-05750	1.80	0.053
49	S07-05751	1.88	0.055
50	S07-05752	1.18	0.034
51	S07-05753	1.25	0.036
52	S07-05754	1.47	0.043
53	S07-05755	1.87	0.054
54	S07-05756	0.77	0.022
55	S07-05757	3.75	0.109
56	S07-05758	<0.03	<0.001
57	S07-05759	1.61	0.047
58	S07-05760	0.53	0.016
59	S07-05761	0.19	0.006
60	S07-05762	0.21	0.006
61	S07-05763	0.13	0.004
62	S07-05764	0.11	0.003
63	S07-05765	0.04	0.001
64	S07-05766	0.13	0.004
65	S07-05767	0.06	0.002
66	S07-05768	2.04	0.059
67	S07-05769	0.14	0.004
68	S07-05770	0.19	0.006
69	S07-05771	0.47	0.014
70	S07-05772	0.22	0.006
71	S07-05773	0.09	0.003


* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
72	S07-05774	<0.03	<0.001
73	S07-05775	0.09	0.003
74	S07-05776	0.25	0.007
75	S07-05777	0.12	0.004
76	S07-05778	0.35	0.010
77	S07-05779	0.04	0.001
78	S07-05780	0.05	0.001
79	S07-05781	0.86	0.025
80	S07-05782	0.43	0.013
81	S07-05783	0.15	0.004
82	S07-05784	0.44	0.013
83	S07-05785	0.04	0.001
84	S07-05786	0.04	0.001
85	S07-05787	0.03	0.001
86	S07-05788	<0.03	<0.001
87	S07-05789	0.12	0.004
88	S07-05790	<0.03	<0.001
89	S07-05791	* <0.03	<0.001
90	S07-05792	0.17	0.005
91	S07-05793	0.37	0.011
92	S07-05794	<0.03	<0.001
93	S07-05795	0.09	0.003
94	S07-05796	0.04	0.001
95	S07-05797	0.16	0.005
96	S07-05798	0.54	0.016
97	S07-05799	0.11	0.003
98	S07-05800	0.26	0.008
99	S07-05801	0.17	0.005
100	S07-05802	0.69	0.020
101	S07-05803	* 0.42	0.012
102	S07-05804	0.14	0.004
103	S07-05805	0.15	0.004
104	S07-05806	0.45	0.013
105	S07-05807	1.85	0.054
106	S07-05808	0.87	0.025
107	S07-05809	1.01	0.030
108	S07-05810	0.14	0.004
109	S07-05811	0.03	0.001
110	S07-05812	0.13	0.004
111	S07-05813	0.04	0.001
112	S07-05814	0.09	0.002
113	S07-05815	0.24	0.007
114	S07-05816	0.06	0.002


* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealousé
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
115	S07-05817	<0.03	<0.001
116	S07-05818	0.05	0.001
117	S07-05819	<0.03	<0.001
118	S07-05820	0.04	0.001
119	S07-05821	0.04	0.001
120	S07-05822	0.06	0.002
121	S07-05823	0.04	0.001
122	S07-05824	<0.03	<0.001
123	S07-05825	<0.03	<0.001
124	S07-05826	<0.03	<0.001
125	S07-05827	<0.03	<0.001
126	S07-05828	2.19	0.064
127	S07-05829	* 6.76	0.197
128	S07-05830	0.35	0.010
129	S07-05831	0.08	0.002
130	S07-05832	0.22	0.006
131	S07-05833	0.42	0.012
132	S07-05834	0.47	0.014
133	S07-05835	1.27	0.037
134	S07-05836	0.12	0.003
135	S07-05837	0.09	0.003
136	S07-05838	0.21	0.006
137	S07-05839	<0.03	<0.001
138	S07-05840	0.38	0.011
139	S07-05841	* <0.03	<0.001
140	S07-05842	0.04	0.001
141	S07-05843	0.03	0.001
142	S07-05844	0.07	0.002
143	S07-05845	0.20	0.006
144	S07-05846	0.03	0.001
145	S07-05847	0.06	0.002
146	S07-05848	<0.03	<0.001
147	S07-05849	<0.03	<0.001
148	S07-05850	<0.03	<0.001
149	S07-05851	<0.03	<0.001
150	S07-05852	<0.03	<0.001
151	S07-05853	<0.03	<0.001
152	S07-05854	0.39	0.011
153	S07-05855	<0.03	<0.001
154	S07-05856	0.04	0.001
155	S07-05857	0.06	0.002
156	S07-05858	0.05	0.002
157	S07-05859	0.07	0.002

* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #		Au (g/t)	Au (oz/t)
158	S07-05860		0.64	0.019
159	S07-05861	*	<0.03	<0.001
160	S07-05862		<0.03	<0.001
161	S07-05863		0.46	0.013
162	S07-05864		0.05	0.001
163	S07-05865		0.12	0.004
164	S07-05866		0.77	0.022
165	S07-05867		0.41	0.012
166	S07-05868		0.05	0.001
167	S07-05869		0.06	0.002
168	S07-05870		0.03	0.001
169	S07-05871		0.44	0.013
170	S07-05872	*	2.08	0.061
171	S07-05873		0.06	0.002
172	S07-05874		0.04	0.001
173	S07-05875		0.08	0.002

QC DATA:**Resplit:**

1	S07-05703	<0.03	<0.001
36	S07-05738	0.20	0.006
71	S07-05773	0.07	0.002
106	S07-05808	0.97	0.028
141	S07-05843	0.14	0.004

Standard:

OXI54	1.90	0.055
OXI54	1.90	0.055
OXI54	1.84	0.054
OXI54	1.84	0.054
OXI54	1.84	0.054
OXI54	1.86	0.054
OXI54	1.86	0.054
OXI54	1.84	0.054
OXI54	1.90	0.055
OXI54	1.90	0.055
OXI54	1.88	0.055
OXI54	1.86	0.054
OXI54	1.88	0.055


1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw
KLS/07


ECO VECH LABORATORY LTD.

 Jutta Jealous
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2300

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

24-Mar-08

Attention: Bob Singh

No. of samples received: 133
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-158
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-05876	<0.03	<0.001
2	S07-05877	<0.03	<0.001
3	S07-05878	<0.03	<0.001
4	S07-05879	<0.03	<0.001
5	S07-05880	<0.03	<0.001
6	S07-05881	<0.03	<0.001
7	S07-05882	<0.03	<0.001
8	S07-05883	<0.03	<0.001
9	S07-05884	<0.03	<0.001
10	S07-05885	<0.03	<0.001
11	S07-05886	<0.03	<0.001
12	S07-05887	<0.03	<0.001
13	S07-05888	<0.03	<0.001
14	S07-05889	<0.03	<0.001
15	S07-05890	<0.03	<0.001
16	S07-05891	<0.03	<0.001
17	S07-05892	<0.03	<0.001
18	S07-05893	0.04	0.001
19	S07-05894	<0.03	<0.001
20	S07-05895	<0.03	<0.001
21	S07-05896	0.04	0.001
22	S07-05897	<0.03	<0.001
23	S07-05898	0.11	0.003
24	S07-05899	0.08	0.002
25	S07-05900	0.17	0.005
26	S07-05901	0.96	0.028
27	S07-05902	0.25	0.007
28	S07-05903	2.04	0.059

ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

* = 30g FA

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	S07-05904	0.23	0.007
30	S07-05905	0.55	0.016
31	S07-05906	0.17	0.005
32	S07-05907	0.06	0.002
33	S07-05908	<0.03	<0.001
34	S07-05909	0.07	0.002
35	S07-05910	0.10	0.003
36	S07-05911	0.24	0.007
37	S07-05912	0.05	0.001
38	S07-05913	0.03	0.001
39	S07-05914	<0.03	<0.001
40	S07-05915	0.11	0.003
41	S07-05916	0.08	0.002
42	S07-05917	0.17	0.005
43	S07-05918	0.06	0.002
44	S07-05919	<0.03	<0.001
45	S07-05920	0.49	0.014
46	S07-05921	0.15	0.004
47	S07-05922	0.12	0.003
48	S07-05923	0.07	0.002
49	S07-05924	0.07	0.002
50	S07-05925	<0.03	<0.001
51	S07-05926	<0.03	<0.001
52	S07-05927	<0.03	<0.001
53	S07-05928	0.24	0.007
54	S07-05929	0.44	0.013
55	S07-05930	0.46	0.013
56	S07-05931	0.45	0.013
57	S07-05932	0.30	0.009
58	S07-05933	<0.03	<0.001
59	S07-05934	0.09	0.003
60	S07-05935	0.24	0.007
61	S07-05936	0.10	0.003
62	S07-05937	<0.03	<0.001
63	S07-05938	<0.03	<0.001
64	S07-05939	<0.03	<0.001
65	S07-05940	<0.03	<0.001
66	S07-05941	2.06	0.060
67	S07-05942	<0.03	<0.001
68	S07-05943	<0.03	<0.001
69	S07-05944	0.11	0.003
70	S07-05945	0.03	0.001
71	S07-05946	<0.03	<0.001
72	S07-05947	<0.03	<0.001
73	S07-05948	<0.03	<0.001

= 30g FA




ECOTECH LABORATORY LTD.

 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
74	S07-05949	<0.03	<0.001
75	S07-05950	0.03	0.001
76	S07-05951	<0.03	<0.001
77	S07-05952	0.06	0.002
78	S07-05953	0.29	0.008
79	S07-05954	0.06	0.002
80	S07-05955	6.71	0.196
81	S07-05956	0.15	0.004
82	S07-05957	0.13	0.004
83	S07-05958	1.35	0.039
84	S07-05959	0.19	0.006
85	S07-05960	0.23	0.007
86	S07-05961	0.06	0.002
87	S07-05962	0.23	0.007
88	S07-05963	<0.03	<0.001
89	S07-05964	<0.03	<0.001
90	S07-05965	<0.03	<0.001
91	S07-05966	<0.03	<0.001
92	S07-05967	<0.03	<0.001
93	S07-05968	<0.03	<0.001
94	S07-05969	0.03	0.001
95	S07-05970	<0.03	<0.001
96	S07-05971	<0.03	<0.001
97	S07-05972	<0.03	<0.001
98	S07-05973	<0.03	<0.001
99	S07-05974	<0.03	<0.001
100	S07-05975	<0.03	<0.001
101	S07-05976	<0.03	<0.001
102	S07-05977	<0.03	<0.001
103	S07-05978	<0.03	<0.001
104	S07-05979	0.03	0.001
105	S07-05980	<0.03	<0.001
106	S07-05981	<0.03	<0.001
107	S07-05982	<0.03	<0.001
108	S07-05983	<0.03	<0.001
109	S07-05984	<0.03	<0.001
110	S07-05985	<0.03	<0.001
111	S07-05986	<0.03	<0.001
112	S07-05987	<0.03	<0.001
113	S07-05988	<0.03	<0.001
114	S07-05989	<0.03	<0.001
115	S07-05990	<0.03	<0.001
116	S07-05991	<0.03	<0.001
117	S07-05992	<0.03	<0.001
118	S07-05993	<0.03	<0.001

= 30g FA


ECCOTECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
119	S07-05994	0.21	0.006
120	S07-05995	<0.03	<0.001
121	S07-05996	10.39	0.303
122	S07-05997	<0.03	<0.001
123	S07-05998	<0.03	<0.001
124	S07-05999	<0.03	<0.001
125	S07-06000	<0.03	<0.001
126	S07-06001	<0.03	<0.001
127	S07-06002	<0.03	<0.001
128	S07-06003	<0.03	<0.001
129	S07-06004	<0.03	<0.001
130	S07-06005	<0.03	<0.001
131	S07-06006	<0.03	<0.001
132	S07-06007	<0.03	<0.001
133	S07-06008	0.36	0.011

QC DATA:**Resplit:**

1	S07-05876	<0.03	<0.001
36	S07-05911	0.35	0.010
71	S07-05946	<0.03	<0.001
106	S07-05981	<0.03	<0.001

Standard:

OXI54	1.84	0.054
OXI54	1.88	0.055
OXI54	1.82	0.053
OXI54	1.80	0.052
OXI54	1.86	0.054
OXI54	1.86	0.054
OXI54	1.82	0.053
OXI54	1.87	0.055
OXI54	1.85	0.054
OXI54	1.90	0.055

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw

XLS/07



ECOTECH LABORATORY LTD.

Jutta Jealous

B.C. Certified Assayer

TECH LABO. LORY LTD.
1 Dallas Drive
LOOPS, B.C.
6T4

ICP CERTIFICATE OF ANALYSIS 2007-2300

Skygold Ventures
615 - 800 W. Pender Street
Vancouver, BC
V6B 2V6

Phone: 250-573-5700
Fax: 250-573-4557

No. of samples received: 133
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-158
Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

#.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
	S07-05876	0.4	6.46	40	765	<5	2.34	<1	17	127	84	3.79	1.84	10	0.84	1541	2	1.71	51	810	28	<5	<20	248	0.17	<10	130	<10	7	81
	S07-05877	<0.2	5.10	10	615	<5	9.93	<1	8	59	40	1.83	2.13	20	0.51	4166	2	0.60	21	410	34	<5	<20	283	0.07	<10	44	<10	12	35
	S07-05878	0.6	5.70	145	520	<5	2.53	<1	22	282	142	3.94	1.96	20	0.76	974	14	0.55	114	760	38	5	<20	83	0.08	<10	150	<10	6	59
	S07-05879	<0.2	4.41	140	540	<5	5.60	<1	23	412	111	3.87	1.05	10	2.07	1318	4	0.62	179	670	30	<5	<20	218	0.05	<10	132	<10	4	71
	S07-05880	<0.2	4.41	165	410	<5	4.28	<1	28	504	37	4.11	0.90	10	2.25	1745	2	0.76	245	640	22	5	<20	180	0.05	<10	87	<10	4	100
	S07-05881	<0.2	5.07	75	445	<5	5.01	<1	33	574	2	4.37	1.49	10	5.80	1917	1	0.76	290	660	22	10	<20	238	0.05	<10	102	<10	5	82
	S07-05882	<0.2	5.64	105	945	<5	3.19	<1	26	307	95	3.56	1.75	10	1.66	1835	1	0.73	177	590	26	<5	<20	133	0.09	<10	60	<10	5	91
	S07-05883	<0.2	4.65	90	445	<5	3.49	<1	27	458	10	3.84	1.19	10	3.31	1403	<1	0.79	232	510	22	5	<20	217	0.05	<10	73	<10	5	106
	S07-05884	<0.2	5.21	115	340	<5	3.82	<1	29	295	72	3.95	1.15	20	1.48	1733	<1	0.80	184	710	30	<5	<20	204	0.08	<10	90	<10	5	79
	S07-05885	<0.2	7.29	<5	485	<5	3.06	<1	10	81	35	4.64	0.97	10	1.34	808	3	2.78	28	870	34	<5	<20	374	0.38	<10	108	<10	17	50
	S07-05886	0.4	2.57	40	165	<5	2.62	<1	11	151	28	2.10	0.63	<10	2.07	888	<1	0.32	86	190	16	<5	<20	101	0.04	<10	76	<10	3	32
	S07-05887	<0.2	3.48	160	70	<5	5.75	<1	45	699	45	4.40	0.87	<10	6.91	1591	<1	0.41	427	460	16	10	<20	193	0.02	<10	113	<10	4	65
	S07-05888	<0.2	3.77	115	70	<5	6.18	<1	54	886	74	5.41	1.03	<10	8.92	1875	<1	0.51	462	630	20	10	<20	225	0.02	<10	131	<10	5	61
	S07-05889	<0.2	3.49	225	120	<5	5.89	<1	44	909	26	4.65	1.16	<10	7.53	2061	<1	0.46	409	510	18	10	<20	253	0.02	<10	96	<10	4	71
	S07-05890	<0.2	4.70	280	205	<5	6.35	<1	37	775	61	5.42	1.49	<10	7.43	2337	<1	0.72	286	760	28	10	<20	292	0.03	<10	136	<10	5	78
	S07-05891	<0.2	3.41	45	80	<5	1.87	<1	18	297	64	3.76	1.52	10	2.81	705	14	0.14	111	580	20	<5	<20	137	0.06	<10	155	<10	4	59
	S07-05892	0.2	4.56	50	110	<5	3.08	<1	23	344	87	4.46	2.03	20	3.31	1066	23	0.21	128	800	30	<5	<20	136	0.07	<10	182	<10	6	76
	S07-05893	<0.2	4.70	50	175	<5	4.34	<1	30	388	86	4.99	1.69	10	4.33	1686	12	0.32	164	770	24	5	<20	193	0.07	<10	147	<10	6	89
	S07-05894	<0.2	5.38	55	405	<5	5.13	<1	38	630	50	4.68	2.28	<10	6.09	2212	<1	0.42	277	690	28	10	<20	257	0.07	<10	131	<10	5	61
	S07-05895	0.4	4.06	55	230	<5	4.58	<1	45	858	53	5.12	1.79	<10	6.93	2083	<1	0.32	374	610	22	20	<20	239	0.03	<10	120	<10	3	64
	S07-05896	<0.2	5.65	45	65	<5	5.00	2	32	561	123	6.14	2.36	20	3.87	1524	27	0.24	211	990	44	5	<20	187	0.08	<10	224	<10	7	168
	S07-05897	<0.2	4.49	30	115	<5	3.51	1	22	505	42	4.05	2.12	10	3.40	1132	12	0.23	153	560	28	5	<20	148	0.06	<10	137	<10	6	131
	S07-05898	0.8	5.50	25	30	<5	3.65	3	21	275	64	5.40	2.15	20	1.77	1097	30	0.17	96	1130	48	10	<20	125	0.09	<10	229	<10	7	178
	S07-05899	<0.2	5.84	10	145	<5	2.33	2	12	159	52	3.37	2.17	20	1.53	690	10	0.21	44	930	38	<5	<20	107	0.12	<10	205	<10	8	157
	S07-05900	<0.2	6.95	10	225	<5	3.47	<1	14	177	56	3.53	2.57	10	1.95	1059	2	0.92	23	650	62	<5	<20	261	0.13	<10	137	<10	9	112

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn	
S07-05901	0.6	6.69	15	40	<5	2.59	<1	18	195	71	4.87	2.78	10	1.28	754	15	0.61	40	860	32	<5	<20	146	0.11	<10	217	<10	6	100
S07-05902	0.6	7.16	10	90	<5	3.71	<1	23	217	52	3.80	2.54	10	1.61	790	6	0.69	26	700	30	<5	<20	154	0.11	<10	135	40	8	65
S07-05903	4.4	4.56	185	310	<5	0.44	1	11	35	601	5.20	2.61	10	1.71	386	7	0.21	24	440	104	45	<20	70	0.28	<10	53	<10	10	682
S07-05904	<0.2	7.66	5	280	<5	4.54	<1	12	106	59	3.27	2.48	10	1.80	1131	1	1.10	15	810	34	<5	<20	184	0.12	<10	103	<10	8	60
S07-05905	<0.2	5.78	20	55	<5	3.24	<1	17	274	73	3.66	2.30	10	1.45	820	8	1.28	34	760	28	<5	<20	161	0.11	<10	160	<10	7	65
S07-05906	0.2	7.20	10	200	<5	3.10	<1	10	148	57	3.40	2.75	20	1.32	771	5	1.24	14	900	26	<5	<20	150	0.16	<10	101	<10	8	67
S07-05907	<0.2	7.41	10	85	<5	5.77	<1	20	133	61	5.73	2.69	20	2.17	1845	<1	1.05	19	1520	30	<5	<20	230	0.19	<10	127	<10	9	96
S07-05908	<0.2	7.74	5	695	<5	3.77	<1	13	64	35	4.76	2.64	20	1.59	1427	<1	1.24	11	1450	32	<5	<20	187	0.20	<10	88	<10	6	84
S07-05909	<0.2	7.65	5	865	<5	3.92	<1	14	68	34	5.25	2.57	20	1.78	1363	<1	1.36	13	1480	28	<5	<20	205	0.17	<10	106	<10	6	89
S07-05910	<0.2	8.00	10	685	<5	3.83	<1	16	71	114	5.11	2.42	20	1.93	1193	<1	1.31	15	1830	36	<5	<20	213	0.17	<10	141	<10	8	83
S07-05911	0.2	7.16	15	95	<5	4.45	<1	17	116	65	5.30	2.40	10	1.57	1319	<1	1.75	20	1000	36	<5	<20	253	0.14	<10	143	<10	7	76
S07-05912	<0.2	7.30	5	220	<5	3.79	<1	16	120	62	4.76	2.63	20	1.55	1340	2	1.48	19	930	34	<5	<20	229	0.16	<10	120	<10	7	94
S07-05913	0.2	7.61	10	270	<5	4.22	<1	14	87	59	4.32	2.71	20	1.52	1323	1	1.55	16	860	32	<5	<20	234	0.15	<10	109	<10	7	81
S07-05914	0.2	7.13	5	990	<5	3.19	<1	12	88	62	4.01	3.01	20	1.82	1111	<1	1.24	16	1090	30	<5	<20	207	0.15	<10	125	<10	7	78
S07-05915	<0.2	7.49	15	535	<5	3.07	<1	18	98	63	4.37	1.84	10	1.59	1186	<1	2.44	27	960	30	<5	<20	228	0.16	<10	129	<10	4	89
S07-05916	0.4	8.56	5	635	<5	3.41	<1	19	96	84	5.22	2.33	10	1.87	1186	<1	2.04	27	890	32	<5	<20	233	0.18	<10	158	<10	4	96
S07-05917	<0.2	7.96	10	600	<5	4.54	<1	21	95	63	5.09	2.35	<10	2.19	1520	<1	2.42	27	880	30	<5	<20	373	0.14	<10	184	<10	4	71
S07-05918	<0.2	8.28	5	455	<5	4.10	<1	22	81	93	5.35	2.19	10	2.21	1340	<1	2.62	37	690	34	<5	<20	438	0.15	<10	200	<10	3	93
S07-05919	<0.2	7.79	10	395	<5	4.30	<1	15	78	59	4.27	1.93	10	1.71	1084	<1	2.73	18	810	32	<5	<20	316	0.16	<10	129	<10	5	64
S07-05920	0.6	9.19	10	615	<5	5.53	<1	17	112	89	5.31	2.48	10	2.18	1298	<1	2.08	23	1070	40	<5	<20	403	0.20	<10	176	<10	6	62
S07-05921	0.4	7.79	15	605	<5	5.83	<1	18	77	79	4.72	2.34	10	2.23	1563	<1	2.31	25	840	30	<5	<20	501	0.18	<10	221	<10	5	57
S07-05922	<0.2	7.97	10	705	<5	4.58	<1	13	104	69	4.42	2.69	10	1.93	1150	<1	1.59	16	910	30	<5	<20	325	0.18	<10	158	<10	5	46
S07-05923	0.2	9.46	10	665	<5	5.37	<1	23	67	71	5.43	2.71	10	2.02	1355	<1	2.35	23	1210	32	15	<20	287	0.23	<10	188	<10	4	67
S07-05924	0.4	9.15	10	695	<5	4.57	<1	16	53	29	4.63	2.91	10	1.93	1144	<1	2.06	18	1020	32	10	<20	372	0.19	<10	175	<10	5	41
S07-05925	<0.2	>10	15	935	<5	6.77	<1	21	56	14	6.30	2.94	<10	2.38	1915	<1	2.69	28	1470	40	<5	<20	554	0.23	<10	205	<10	6	42
S07-05926	<0.2	9.27	10	805	<5	6.16	<1	16	44	18	5.37	2.89	10	2.42	1535	<1	3.44	20	1230	32	<5	<20	526	0.20	<10	210	<10	6	37
S07-05927	<0.2	8.86	10	735	<5	5.92	<1	16	48	8	5.10	2.80	10	2.41	1453	<1	3.14	20	1230	32	<5	<20	527	0.19	<10	202	<10	7	33
S07-05928	<0.2	8.70	20	580	<5	5.85	<1	20	26	39	7.34	2.52	20	2.33	1541	<1	3.17	16	2180	36	<5	<20	545	0.27	<10	226	<10	10	49
S07-05929	0.4	7.26	10	490	<5	4.43	<1	16	54	182	6.36	2.28	10	1.61	1284	1	2.24	12	2000	32	<5	<20	347	0.25	<10	207	<10	8	66
S07-05930	0.4	7.94	15	420	<5	5.61	<1	19	38	128	7.03	2.20	20	2.12	1694	<1	2.88	13	2380	36	<5	<20	557	0.31	<10	218	<10	10	68
S07-05931	<0.2	8.31	30	130	<5	6.75	<1	23	43	10	7.05	1.78	20	2.17	1828	7	3.77	15	2480	38	<5	<20	699	0.41	<10	212	<10	11	43
S07-05932	<0.2	8.12	5	220	<5	4.30	<1	15	56	54	5.25	1.18	20	1.71	1254	1	4.89	15	1740	32	<5	<20	516	0.29	<10	140	<10	8	38
S07-05933	<0.2	0.08	<5	20	<5	>10	<1	<1	2	2	0.54	0.03	<10	>10	201	<1	0.04	3	190	<2	<5	<20	45	<0.01	<10	4	<10	<1	13
S07-05934	<0.2	7.71	5	500	<5	3.20	<1	14	84	64	4.42	1.96	10	1.52	1057	<1	3.12	14	1170	30	5	<20	349	0.22	<10	153	<10	6	78
S07-05935	<0.2	7.09	15	565	<5	3.37	<1	9	104	33	3.73	2.59	20	1.06	789	2	1.97	15	980	30	<5	<20	279	0.24	<10	119	<10	6	83
S07-05936	<0.2	7.43	10	885	<5	3.53	<1	12	87	51	4.46	2.82	10	1.54	972	2	2.26	16	960	32	<5	<20	281	0.22	<10	170	<10	5	61
S07-05937	0.2	8.06	10	850	<5	3.91	<1	16	96	195	5.01	3.12	<10	1.69	1226	<1	1.56	19	1020	34	<5	<20	251	0.23	<10	155	<10	5	76
S07-05938	<0.2	7.45	<5	840	<5	3.79	<1	9	65	30	3.59	2.87	10	1.22	940	<1	1.69	11	840	28	<5	<20	247	0.20	<10	98	<10	4	54
S07-05939	<0.2	7.57	<5	705	<5	4.31	<1	12	51	40	4.25	2.74	10	1.40	1189	<1	1.77	13	1160	30	<5	<20	256	0.21	<10	113	<10	5	64
S07-05940	0.2	7.42	<5	590	<5	3.50	<1	11	53	27	4.25	2.42	10	1.31	1145	<1	1.96	13	1020	28	<5	<20	289	0.22	<10	105	<10	5	70


Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Li	mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn	
S07-05941	4.6	4.51	115	305	<5	0.43	1	11	37	613	5.40	2.67	10	1.69	382	7	0.25	23	430	106	45	<20	70	0.28	<10	54	<10	10	672
S07-05942	<0.2	7.83	<5	580	<5	3.95	<1	12	51	38	4.38	2.57	10	1.42	1181	<1	2.06	12	890	28	<5	<20	278	0.21	<10	131	<10	5	65
S07-05943	0.4	7.67	5	765	<5	4.19	<1	9	71	26	3.64	3.21	20	1.38	1027	<1	1.36	10	750	30	<5	<20	268	0.17	<10	97	<10	6	51
S07-05944	0.2	7.55	5	575	<5	3.71	<1	10	68	44	3.76	2.23	10	1.32	989	<1	2.56	12	770	28	<5	<20	316	0.20	<10	105	<10	6	46
S07-05945	<0.2	7.07	<5	675	<5	3.25	<1	7	59	38	2.63	2.53	20	1.00	762	<1	1.76	8	620	30	<5	<20	337	0.18	<10	65	<10	7	39
S07-05946	<0.2	7.98	<5	515	<5	3.35	<1	13	59	46	4.39	1.68	10	1.54	1044	<1	3.09	14	730	28	<5	<20	355	0.25	<10	138	<10	5	66
S07-05947	<0.2	8.65	<5	680	<5	3.51	<1	19	53	68	5.30	2.17	<10	1.93	1214	<1	2.66	18	770	32	<5	<20	360	0.26	<10	187	<10	4	76
S07-05948	<0.2	8.02	15	690	<5	3.56	<1	22	74	75	5.26	2.24	10	1.78	1088	<1	1.98	27	680	30	<5	<20	370	0.22	<10	176	<10	3	78
S07-05949	<0.2	8.08	5	595	<5	3.29	<1	17	60	64	4.19	2.29	10	1.49	1035	<1	3.10	13	710	28	<5	<20	275	0.28	<10	132	<10	5	55
S07-05950	0.2	7.84	<5	505	<5	4.06	<1	16	61	41	4.51	2.53	<10	1.66	1179	<1	2.38	14	720	28	<5	<20	302	0.26	<10	156	<10	4	45
S07-05951	<0.2	9.26	5	770	<5	4.06	<1	20	57	61	5.60	2.93	<10	1.85	1232	<1	2.35	20	930	32	<5	<20	299	0.26	<10	185	<10	3	71
S07-05952	<0.2	7.71	<5	575	<5	3.69	<1	15	90	51	4.32	2.29	<10	1.49	945	<1	2.74	15	770	28	<5	<20	337	0.22	<10	152	<10	5	56
S07-05953	<0.2	8.13	5	750	<5	3.11	<1	16	57	61	4.71	2.60	<10	1.59	961	<1	2.80	15	760	32	<5	<20	322	0.24	<10	165	<10	4	71
S07-05954	<0.2	8.13	5	615	<5	2.90	<1	11	69	104	4.52	2.13	10	1.44	960	<1	3.12	12	950	232	<5	<20	287	0.23	<10	119	<10	4	143
S07-05955	6.3	3.93	135	340	<5	0.42	<1	7	42	58	3.56	2.99	<10	0.25	233	6	0.55	22	400	26	60	<20	91	0.33	<10	53	<10	9	56
S07-05956	<0.2	8.28	5	620	<5	3.93	<1	17	62	53	5.13	2.18	<10	1.71	1268	<1	3.15	15	930	28	<5	<20	420	0.27	<10	163	<10	4	63
S07-05957	<0.2	8.29	5	735	<5	4.37	<1	19	78	66	5.69	2.64	<10	2.00	1345	<1	2.35	20	880	52	<5	<20	423	0.27	<10	208	<10	4	49
S07-05958	1.4	7.15	5	320	<5	3.01	3	17	67	151	4.77	1.43	<10	1.40	1022	<1	4.57	15	840	48	<5	<20	365	0.23	<10	152	<10	4	266
S07-05959	<0.2	7.66	<5	540	<5	2.93	<1	21	67	97	5.57	1.89	<10	1.79	1200	<1	3.83	16	670	30	<5	<20	372	0.27	<10	206	<10	3	86
S07-05960	<0.2	6.73	<5	370	<5	2.76	<1	16	103	52	4.23	1.49	<10	1.41	986	<1	3.80	16	700	32	<5	<20	364	0.21	<10	155	<10	4	39
S07-05961	<0.2	6.21	5	195	<5	2.13	<1	11	70	38	3.94	0.85	<10	1.21	884	<1	4.63	12	810	26	<5	<20	276	0.25	<10	111	<10	4	58
S07-05962	<0.2	6.64	10	290	<5	2.72	<1	16	110	25	4.31	1.13	10	1.76	841	<1	4.04	26	890	28	<5	<20	299	0.25	<10	144	<10	5	61
S07-05963	<0.2	7.07	15	830	<5	4.27	<1	27	163	31	5.72	2.20	<10	3.45	1174	<1	2.12	55	900	24	<5	<20	351	0.20	<10	204	<10	5	72
S07-05964	<0.2	6.83	15	925	<5	4.54	<1	28	161	59	5.60	2.45	<10	3.95	1155	<1	1.77	55	880	26	<5	<20	440	0.18	<10	222	<10	6	57
S07-05965	<0.2	0.09	<5	25	<5	>10	<1	<1	2	1	0.56	0.03	<10	>10	197	<1	0.02	2	170	2	<5	<20	54	<0.01	<10	3	<10	<1	14
S07-05966	<0.2	7.61	15	780	<5	4.71	<1	32	123	70	6.10	2.41	<10	3.50	1178	<1	2.32	53	970	30	<5	<20	393	0.20	<10	222	<10	5	69
S07-05967	<0.2	7.56	5	590	<5	4.40	<1	22	88	73	5.80	1.92	<10	2.95	1165	<1	2.78	30	990	28	<5	<20	440	0.26	<10	242	<10	5	58
S07-05968	<0.2	7.79	5	305	<5	3.88	<1	20	63	84	5.52	1.22	<10	2.31	1108	<1	3.81	22	900	28	<5	<20	505	0.26	<10	234	<10	4	59
S07-05969	<0.2	8.42	10	240	<5	4.16	<1	21	80	99	5.93	1.38	10	2.24	1118	<1	3.88	26	1060	32	<5	<20	536	0.29	<10	246	<10	5	60
S07-05970	<0.2	8.15	5	135	<5	4.68	<1	22	66	88	5.86	0.50	<10	2.32	1182	<1	4.17	25	1020	30	<5	<20	561	0.34	<10	227	<10	5	70
S07-05971	<0.2	7.72	5	235	<5	3.22	<1	23	72	107	5.64	0.61	<10	2.23	921	<1	4.35	29	940	28	<5	<20	357	0.37	<10	257	<10	5	69
S07-05972	<0.2	7.81	10	240	<5	3.77	<1	25	144	137	6.10	0.89	<10	3.13	1101	<1	3.99	56	1090	26	5	<20	348	0.30	<10	224	<10	5	64
S07-05973	<0.2	6.73	20	900	<5	4.40	<1	29	248	158	5.93	1.55	10	3.84	1160	<1	2.43	93	1060	26	<5	<20	354	0.15	<10	232	<10	6	57
S07-05974	<0.2	7.15	20	930	<5	5.12	<1	32	261	128	6.42	1.57	10	3.86	1153	<1	2.67	93	1150	30	<5	<20	423	0.15	<10	254	<10	7	60
S07-05975	<0.2	6.80	20	745	<5	3.82	<1	28	237	98	6.02	1.37	10	3.85	1032	<1	2.67	83	1170	32	<5	<20	412	0.14	<10	216	<10	6	63
S07-05976	<0.2	7.13	15	795	<5	4.11	<1	30	244	103	6.34	1.39	10	3.94	1066	<1	2.79	83	1230	32	<5	<20	424	0.14	<10	231	<10	6	67
S07-05977	<0.2	6.89	15	1145	<5	5.12	<1	27	166	130	5.83	1.56	10	3.47	1085	<1	2.82	69	1140	30	<5	<20	459	0.17	<10	227	<10	6	55
S07-05978	<0.2	6.85	10	670	<5	3.91	<1	28	197	177	5.73	0.71	10	3.37	887	<1	3.35	78	1040	30	<5	<20	343	0.19	<10	322	<10	6	55
S07-05979	<0.2	7.00	10	400	<5	3.67	<1	31	192	157	6.10	0.68	10	3.58	1049	<1	3.26	79	1140	28	<5	<20	355	0.22	<10	274	<10	6	61
S07-05980	<0.2	7.26	10	315	<5	3.75	<1	27	176	96	5.99	0.75	<10	3.74	1120	<1	3.51	66	1120	28	<5	<20	392	0.22	<10	216	<10	6	65


	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Lg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn			
3	S07-05981	<0.2	7.68	10	270	<5	3.98	<1	30	205	150	6.38	0.51	10	3.92	1165	<1	3.63	81	1260	44	<5	<20	431	0.24	<10	254	<10	7	79	
7	S07-05982	<0.2	6.88	10	440	<5	5.09	<1	31	332	120	6.27	1.03	10	4.25	1324	<1	2.89	97	1290	36	<5	<20	499	0.15	<10	211	<10	7	58	
3	S07-05983	<0.2	7.04	15	550	<5	5.33	<1	34	457	66	6.54	0.92	<10	4.64	1319	<1	2.57	138	1180	34	5	<20	428	0.13	<10	215	<10	7	76	
3	S07-05984	<0.2	7.04	25	530	<5	5.47	<1	34	427	95	5.63	0.68	<10	3.99	1172	<1	3.12	130	1030	34	<5	<20	421	0.12	<10	269	<10	6	59	
3	S07-05985	0.2	6.66	20	640	<5	5.03	<1	31	418	53	6.03	0.88	10	4.36	1165	<1	2.45	111	1120	38	<5	<20	384	0.12	<10	228	<10	8	69	
1	S07-05986	<0.2	8.32	10	1740	<5	3.72	<1	21	152	75	5.77	1.69	10	3.59	1170	<1	3.05	41	1250	36	<5	<20	381	0.20	<10	249	<10	7	56	
2	S07-05987	<0.2	8.45	5	1740	<5	3.91	<1	25	125	55	5.72	1.81	10	3.39	1287	<1	2.99	39	1260	42	<5	<20	372	0.19	<10	233	<10	7	65	
3	S07-05988	<0.2	8.19	10	1635	<5	3.25	<1	22	130	89	5.61	1.70	10	3.03	1213	<1	3.15	33	1160	40	<5	<20	349	0.19	<10	207	<10	6	61	
1	S07-05989	<0.2	8.25	10	1790	<5	3.12	<1	23	135	67	5.60	2.12	<10	2.80	1168	<1	2.98	34	1070	42	<5	<20	303	0.21	<10	224	<10	5	59	
5	S07-05990	<0.2	9.02	5	1905	<5	3.14	<1	22	141	77	5.99	2.13	10	2.86	1253	<1	3.18	34	1090	50	<5	<20	309	0.22	<10	227	<10	5	68	
3	S07-05991	<0.2	9.23	10	1870	<5	3.28	<1	21	110	90	6.02	1.91	10	2.70	1134	<1	3.38	34	1310	46	<5	<20	318	0.27	<10	228	<10	6	66	
7	S07-05992	0.2	8.70	10	1625	<5	3.73	<1	23	97	84	5.62	1.65	10	2.74	1131	<1	3.40	33	1190	40	<5	<20	352	0.28	<10	219	<10	7	62	
3	S07-05993	0.2	8.48	10	1485	<5	3.70	<1	25	99	95	5.53	1.79	10	2.89	1083	<1	3.27	35	1200	44	<5	<20	350	0.29	<10	220	<10	7	60	
3	S07-05994	<0.2	8.58	15	1645	<5	4.59	<1	25	115	63	5.72	2.50	10	3.39	1381	<1	2.55	41	1260	68	<5	<20	382	0.22	<10	224	<10	7	58	
3	S07-05995	<0.2	8.48	10	1390	<5	4.00	<1	26	119	53	5.99	2.21	<10	3.43	1239	<1	3.04	42	1230	42	<5	<20	374	0.22	<10	231	<10	7	71	
1	S07-05996	3.4	>10	150	1385	<5	8.85	<1	101	664	64	>10	2.99	20	7.41	2359	<1	3.21	266	2580	828	10	<20	796	0.19	<10	437	<10	14	114	
2	S07-05997	<0.2	6.59	25	755	<5	4.55	<1	38	462	81	6.31	1.86	10	4.69	1176	<1	1.85	138	1040	42	<5	<20	356	0.12	<10	249	<10	7	67	
3	S07-05998	<0.2	6.87	15	765	<5	4.07	<1	29	351	121	5.91	1.94	10	4.09	1097	<1	1.95	101	1220	40	5	<20	341	0.15	<10	228	<10	7	70	
1	S07-05999	0.4	6.86	15	815	<5	4.50	<1	28	259	128	5.99	2.03	<10	3.88	1171	<1	1.88	84	1070	46	<5	<20	423	0.12	<10	208	<10	7	62	
5	S07-06000	0.6	7.33	15	915	<5	3.68	<1	29	218	109	6.37	1.97	10	3.44	1147	<1	2.42	77	1260	46	<5	<20	366	0.18	<10	218	<10	6	73	
3	S07-06001	<0.2	0.10	<5	25	<5	>10	<1	<1	2	2	0.55	0.03	<10	>10	197	<1	0.02	3	200	10	<5	<20	93	<0.01	<10	3	<10	<1	12	
7	S07-06002	0.4	7.28	20	815	<5	4.34	<1	22	140	124	5.45	1.51	10	2.52	1000	1	3.45	45	1350	52	<5	<20	421	0.21	<10	222	<10	7	100	
3	S07-06003	<0.2	7.36	15	1315	<5	4.27	<1	26	162	69	5.95	2.15	10	3.27	1268	<1	2.35	60	1370	42	<5	<20	409	0.21	<10	225	<10	7	76	
3	S07-06004	0.4	7.63	15	1365	<5	4.33	<1	30	179	110	6.23	2.06	10	3.31	1165	<1	2.57	69	1330	40	<5	<20	394	0.21	<10	261	<10	6	83	
3	S07-06005	<0.2	6.31	15	1355	<5	4.72	<1	28	226	92	5.75	2.09	<10	3.95	1198	<1	2.18	82	1040	38	5	<20	555	0.14	<10	268	<10	6	57	
1	S07-06006	0.4	6.28	25	1325	<5	5.49	<1	28	305	90	6.10	1.98	<10	4.23	1415	<1	1.98	102	1040	58	5	<20	667	0.12	<10	241	<10	6	137	
2	S07-06007	<0.2	6.42	135	1380	<5	6.62	<1	36	383	35	5.94	1.95	10	3.97	1333	<1	2.42	126	1030	34	<5	<20	865	0.11	<10	202	<10	7	54	
3	S07-06008	<0.2	7.08	15	810	<5	3.54	<1	23	206	63	5.22	1.40	<10	2.42	1033	<1	3.73	45	1150	44	<5	<20	656	0.18	<10	217	<10	6	61	
ATA:																															
at:																															
	S07-05876	0.6	6.54	40	780	<5	2.45	<1	16	124	84	3.67	1.84	20	0.87	1572	1	1.79	50	820	32	<5	<20	255	0.17	<10	132	<10	7	86	
	S07-05886	0.3	2.41	45	155	<5	2.57	<1	11	150	25	2.03	0.59	<10	1.98	864	<1	0.30	82	180	18	<5	<20	98	0.04	<10	74	<10	3	32	
	S07-05894	0.2	5.24	45	395	<5	4.92	<1	39	590	47	4.77	2.18	<10	5.98	2166	<1	0.45	254	640	25	10	<20	252	0.06	<10	121	<10	5	59	
	S07-05911	0.2	7.17	15	105	<5	4.49	<1	18	116	61	5.33	2.36	10	1.58	1318	<1	1.79	19	1010	38	<5	<20	250	0.14	<10	142	<10	7	74	
	S07-05920	0.2	8.78	15	605	<5	5.40	<1	16	107	91	5.02	2.48	10	2.10	1255	<1	2.17	21	940	36	<5	<20	394	0.19	<10	170	<10	6	56	
	S07-05929	0.4	7.21	<5	515	<5	4.52	<1	19	53	182	6.11	2.35	20	1.63	1307	1	2.30	12	2000	32	<5	<20	360	0.28	<10	220	<10	9	66	
	S07-05946	<0.2	8.23	5	525	<5	3.51	<1	14	52	47	4.60	1.70	10	1.58	1106	<1	3.32	15	770	26	<5	<20	363	0.26	<10	140	<10	5	69	
	S07-05964	<0.2	7.06	10	930	<5	4.65	<1	27	160	60	5.89	2.42	<10	3.94	1231	<1	1.81	55	930	32	<5	<20	438	0.19	<10	221	<10	5	61	
3	S07-05981	<0.2	7.58	10	270	<5	3.96	<1	27	206	152	6.31	0.52	10	3.93	1147	<1	3.50	79	1240	42	<5	<20	432	0.23	<10	251	<10	7	85	
3	S07-05990	0.2	8.93	10	1895	<5	3.18	<1	23	139	75	5.86	2.12	10	2.90	1212	<1	3.16	34	1050	46	<5	<20	313	0.21	<10	226	<10	5	83	
1	S07-05999	0.4	7.03	15	850	<5	4.60	<1	29	275	135	6.23	2.14	10	4.06	1235	<1	1.94	90	1130	50	<5	<20	438	0.13	<10	216	<10	7	64	

#.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Li%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
<i>nit:</i>																														
	S07-05876	0.6	6.69	35	725	<5	2.12	<1	15	122	81	3.98	1.75	10	0.78	1525	2	1.79	49	830	28	<5	<20	259	0.19	<10	131	<10	8	77
	S07-05911	0.3	7.02	10	110	<5	4.32	<1	19	110	62	4.90	2.66	20	1.66	1224	<1	1.66	20	960	32	<5	<20	245	0.15	<10	152	<10	7	75
	S07-05946	<0.2	8.12	5	555	<5	3.54	<1	14	64	46	4.49	1.80	<10	1.62	1054	<1	2.88	16	750	28	<5	<20	371	0.27	<10	140	<10	5	76
	S07-05981	0.4	7.46	10	255	<5	3.70	<1	26	189	164	6.04	0.52	10	3.89	1133	<1	3.52	73	1210	40	<5	<20	428	0.22	<10	246	<10	6	76
<i>dard:</i>																														
		0.4	5.61	20	1285	<5	2.30	<1	15	58	33	4.10	1.47	30	1.31	2529	5	1.35	33	2330	58	<5	<20	313	0.37	<10	101	<10	27	191
		0.5	5.68	20	1245	<5	2.38	<1	15	59	33	4.13	1.42	30	1.33	2590	5	1.28	34	2260	60	<5	<20	316	0.35	<10	112	<10	28	199
		0.4	5.73	20	1270	<5	2.38	<1	15	60	34	4.09	1.43	30	1.35	2517	5	1.27	33	2300	62	<5	<20	320	0.35	<10	111	<10	29	192
		0.4	5.82	20	1255	<5	2.38	<1	15	58	34	4.16	1.45	30	1.36	2574	5	1.34	32	2270	70	<5	<20	323	0.34	<10	103	<10	28	208

4 ACID DIGEST/ICP-FINISH
4 ACID DIGEST/AA-FINISH

00s
07


TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: Info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2298

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC


20-Mar-08

Attention: Bob Singh

No. of samples received: 216
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-159
Samples submitted by: Tasha Gainer

Metallic Assays


ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-19402	<0.03	<0.001
2	S07-19403	0.20	0.006
3	S07-19404	0.34	0.010
4	S07-19405	<0.03	<0.001
5	S07-19406	<0.03	<0.001
6	S07-19407	* 0.42	0.012
7	S07-19408	<0.03	<0.001
8	S07-19409	<0.03	<0.001
9	S07-19410	<0.03	<0.001
10	S07-19411	0.04	0.001
11	S07-19412	<0.03	<0.001
12	S07-19413	<0.03	<0.001
13	S07-19414	0.05	0.001
14	S07-19415	0.03	0.001
15	S07-19416	<0.03	<0.001
16	S07-19417	0.87	0.025
17	S07-19418	0.16	0.005
18	S07-19419	<0.03	<0.001
19	S07-19420	<0.03	<0.001
20	S07-19421	<0.03	<0.001
21	S07-19422	<0.03	<0.001
22	S07-19423	<0.03	<0.001
23	S07-19424	<0.03	<0.001
24	S07-19425	<0.03	<0.001
25	S07-19426	<0.03	<0.001
26	S07-19427	<0.03	<0.001
27	S07-19428	<0.03	<0.001
28	S07-19429	<0.03	<0.001


ECO TECH LABORATORY LTD.
Jutta Jealous

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	S07-19430	0.11	0.003
30	S07-19431	<0.03	<0.001
31	S07-19432	<0.03	<0.001
32	S07-19433	<0.03	<0.001
33	S07-19434	<0.03	<0.001
34	S07-19435	0.03	0.001
35	S07-19436	<0.03	<0.001
36	S07-19437	<0.03	<0.001
37	S07-19438	<0.03	<0.001
38	S07-19439	<0.03	<0.001
39	S07-19440	<0.03	<0.001
40	S07-19441	<0.03	<0.001
41	S07-19442	3.36	0.098
42	S07-19443	<0.03	<0.001
43	S07-19444	<0.03	<0.001
44	S07-19445	<0.03	<0.001
45	S07-19446	<0.03	<0.001
46	S07-19447	<0.03	<0.001
47	S07-19448	<0.03	<0.001
48	S07-19449	<0.03	<0.001
49	S07-19450	<0.03	<0.001
50	S07-19451	0.06	0.002
51	S07-19452	<0.03	<0.001
52	S07-19453	<0.03	<0.001
53	S07-19454	<0.03	<0.001
54	S07-19455	<0.03	<0.001
55	S07-19456	0.09	0.003
56	S07-19457	<0.03	<0.001
57	S07-19458	<0.03	<0.001
58	S07-19459	6.69	0.195
59	S07-19460	<0.03	<0.001
60	S07-19461	0.08	0.002
61	S07-19462	0.11	0.003
62	S07-19463	0.16	0.005
63	S07-19464	0.22	0.006
64	S07-19465	0.12	0.004
65	S07-19466	0.16	0.005
66	S07-19467	0.17	0.005
67	S07-19468	0.17	0.005
68	S07-19469	0.18	0.005
69	S07-19470	0.22	0.007
70	S07-19471	0.16	0.005
71	S07-19472	0.20	0.006


* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
72	S07-19473	0.17	0.005
73	S07-19474	0.44	0.013
74	S07-19475	0.20	0.006
75	S07-19476	0.13	0.004
76	S07-19477	2.03	0.059
77	S07-19478	0.19	0.006
78	S07-19479	0.21	0.006
79	S07-19480	0.20	0.006
80	S07-19481	0.21	0.006
81	S07-19482	0.18	0.005
82	S07-19483	0.18	0.005
83	S07-19484	0.20	0.006
84	S07-19485	0.26	0.008
85	S07-19486	0.20	0.006
86	S07-19487	0.18	0.005
87	S07-19488	0.16	0.005
88	S07-19489	0.15	0.004
89	S07-19490	0.10	0.003
90	S07-19491	0.09	0.003
91	S07-19492	0.12	0.003
92	S07-19493	0.33	0.010
93	S07-19494	0.35	0.010
94	S07-19495	0.07	0.002
95	S07-19496	0.16	0.005
96	S07-19497	0.14	0.004
97	S07-19498	0.10	0.003
98	S07-19499	<0.03	<0.001
99	S07-19500	0.14	0.004
100	S07-19501	0.13	0.004
101	S07-19502	0.22	0.006
102	S07-19503	0.15	0.004
103	S07-19504	0.32	0.009
104	S07-19505	0.71	0.021
105	S07-19506	0.78	0.023
106	S07-19507	1.34	0.039
107	S07-19508	1.28	0.037
108	S07-19509	0.27	0.008
109	S07-19510	0.32	0.009
110	S07-19511	0.69	0.020
111	S07-19512	0.11	0.003
112	S07-19513	0.13	0.004
113	S07-19514	0.52	0.015
114	S07-19515	<0.03	<0.001


* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
115	S07-19516	<0.03	<0.001
116	S07-19517	<0.03	<0.001
117	S07-19518	0.18	0.005
118	S07-19519	0.09	0.003
119	S07-19520	<0.03	<0.001
120	S07-19521	0.25	0.007
121	S07-19522	0.07	0.002
122	S07-19523	0.12	0.003
123	S07-19524	0.06	0.002
124	S07-19525	0.03	0.001
125	S07-19526	* <0.03	<0.001
126	S07-19527	0.03	0.001
127	S07-19528	<0.03	<0.001
128	S07-19529	<0.03	<0.001
129	S07-19530	<0.03	<0.001
130	S07-19531	0.03	0.001
131	S07-19532	<0.03	<0.001
132	S07-19533	0.65	0.019
133	S07-19534	* 0.43	0.013
134	S07-19535	0.56	0.016
135	S07-19536	0.95	0.028
136	S07-19537	0.89	0.026
137	S07-19538	0.29	0.008
138	S07-19539	1.07	0.031
139	S07-19540	0.30	0.009
140	S07-19541	<0.03	<0.001
141	S07-19542	0.57	0.017
142	S07-19543	0.44	0.013
143	S07-19544	0.15	0.004
144	S07-19545	3.12	0.091
145	S07-19546	0.04	0.001
146	S07-19547	<0.03	<0.001
147	S07-19548	0.06	0.002
148	S07-19549	7.71	0.225
149	S07-19550	0.10	0.003
150	S07-19551	<0.03	<0.001
151	S07-19552	0.05	0.002
152	S07-19553	<0.03	<0.001
153	S07-19554	<0.03	<0.001
154	S07-19555	* <0.03	<0.001
155	S07-19556	0.03	0.001
156	S07-19557	<0.03	<0.001
157	S07-19558	<0.03	<0.001

* = 30g FA




ECO TECH LABORATORY LTD.
Jutta Jealous
P. C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
158	S07-19559	<0.03	<0.001
159	S07-19560	<0.03	<0.001
160	S07-19561	<0.03	<0.001
161	S07-19562	5.89	0.172
162	S07-19563	0.03	0.001
163	S07-19564	<0.03	<0.001
164	S07-19565	6.57	0.192
165	S07-19566	<0.03	<0.001
166	S07-19567	0.23	0.007
167	S07-19568	<0.03	<0.001
168	S07-19569	<0.03	<0.001
169	S07-19570	<0.03	<0.001
170	S07-19571	<0.03	<0.001
171	S07-19572	<0.03	<0.001
172	S07-19573	<0.03	<0.001
173	S07-19574	<0.03	<0.001
174	S07-19575	<0.03	<0.001
175	S07-19576	<0.03	<0.001
176	S07-19577	<0.03	<0.001
177	S07-19578	<0.03	<0.001
178	S07-19579	1.09	0.032
179	S07-19580	<0.03	<0.001
180	S07-19581	<0.03	<0.001
181	S07-19582	<0.03	<0.001
182	S07-19583	0.08	0.002
183	S07-19584	0.12	0.004
184	S07-19585	0.07	0.002
185	S07-19586	0.02	0.001
186	S07-19587	0.05	0.002
187	S07-19588	<0.03	<0.001
188	S07-19589	0.03	0.001
189	S07-19590	<0.03	<0.001
190	S07-19591	<0.03	<0.001
191	S07-19592	<0.03	<0.001
192	S07-19593	<0.03	<0.001
193	S07-19594	0.05	0.002
194	S07-19595	0.03	0.001
195	S07-19596	<0.03	<0.001
196	S07-19597	0.03	0.001
197	S07-19598	<0.03	<0.001
198	S07-19599	0.04	0.001
199	S07-19600	0.04	0.001
200	S07-19601	0.26	0.008

* = 30g FA



ECO TECH LABORATORY LTD.
R.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
201	S07-19602	<0.03	<0.001
202	S07-19603	0.06	0.002
203	S07-19604	2.00	0.058
204	S07-19605	0.09	0.003
205	S07-19606	<0.03	<0.001
206	S07-19607	<0.03	<0.001
207	S07-19608	0.09	0.003
208	S07-19609	0.48	0.014
209	S07-19610	0.04	0.001
210	S07-19611	<0.03	<0.001
211	S07-19612	<0.03	<0.001
212	S07-19613	<0.03	<0.001
213	S07-19614	0.03	0.001
214	S07-19615	0.10	0.003
215	S07-19616	<0.03	<0.001
216	S07-19617	<0.03	<0.001

QC DATA:**Resplit:**

1	S07-19402	<0.03	<0.001
36	S07-19437	<0.03	<0.001
71	S07-19472	0.23	0.007
106	S07-19507	1.84	0.054
141	S07-19542	0.36	0.011
176	S07-19577	<0.03	<0.001
211	S07-19612	0.07	0.002

Standard:

OXI54	1.83	0.053
OXI54	1.85	0.054
OXI54	1.86	0.054
OXI54	1.84	0.054
OXI54	1.80	0.052
OXI54	1.89	0.055
OXI54	1.86	0.054
OXI54	1.83	0.053
OXI54	1.89	0.055
OXI54	1.80	0.052
OXI54	1.82	0.053
OXI54	1.86	0.054
OXI54	1.84	0.054
OXI54	1.85	0.054
OXI54	1.89	0.055
OXI54	1.88	0.055
OXI54	1.87	0.055
OXI54	1.84	0.054

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw

M 0 0 0 0



ECO TECH LABORATORY LTD.

Jutta Jealous

CH LABORATORY LTD.
 3115 Millar Drive
 Vancouver, B.C.

ICP CERTIFICATE OF ANALYSIS A. 07-2298

Skygold Ventures
 615 - 800 W. Pender Street
 Vancouver, BC
 V6B 2V6

50-573-5700
 50-573-4557

No. of samples received: 216

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-159

Samples submitted by: Tasha Gainer

in ppm unless otherwise reported

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
S07-19402	0.4	4.90	45	655	<5	0.93	<1	20	103	58	2.91	1.78	10	0.97	1704	<1	0.70	47	550	28	<5	<20	91	0.16	<10	113	<10	6	54
S07-19403	0.4	4.74	50	500	<5	0.60	<1	17	168	86	2.95	2.13	20	0.77	1830	<1	0.26	48	570	28	<5	<20	62	0.11	<10	89	<10	5	54
S07-19404	1.0	5.60	60	1335	<5	1.96	<1	23	197	238	3.46	2.72	30	1.32	2737	<1	0.24	68	520	40	15	<20	142	0.14	<10	125	<10	8	103
S07-19405	1.0	4.29	70	1105	<5	0.77	<1	23	154	52	3.36	1.81	20	0.99	2287	<1	0.19	64	500	26	<5	<20	69	0.11	<10	55	<10	6	90
S07-19406	0.4	4.28	30	1095	<5	0.66	<1	20	139	57	3.53	1.76	30	1.33	2148	<1	0.43	64	440	28	<5	<20	59	0.11	<10	64	<10	6	81
S07-19407	0.9	5.92	85	200	<5	0.24	<1	7	22	30	3.43	4.51	10	0.33	162	3	0.10	15	510	22	35	<20	49	0.35	<10	62	<10	10	43
S07-19408	0.4	5.17	15	1435	<5	1.03	<1	8	196	15	2.32	2.02	10	1.30	1778	<1	0.57	20	450	26	<5	<20	93	0.10	<10	50	<10	5	61
S07-19409	0.4	4.64	30	1225	<5	0.98	<1	18	217	54	3.47	1.84	20	1.51	2240	<1	0.73	63	480	28	<5	<20	90	0.11	<10	94	<10	6	89
S07-19410	0.6	4.77	35	1170	<5	1.37	<1	24	352	47	3.63	2.16	20	2.14	2463	<1	0.27	90	490	24	<5	<20	113	0.11	<10	97	<10	6	94
S07-19411	0.2	2.77	20	560	<5	3.08	<1	13	195	21	3.11	1.29	20	2.42	2909	<1	0.10	43	310	16	<5	<20	252	0.05	<10	66	<10	7	57
S07-19412	0.8	3.99	10	1300	<5	1.04	<1	10	184	135	2.01	1.89	20	1.20	1551	<1	0.21	28	270	22	<5	<20	92	0.09	<10	85	<10	6	47
S07-19413	0.4	5.60	<5	1855	<5	0.99	<1	3	81	5	1.72	2.23	20	1.13	1959	<1	0.98	9	320	22	<5	<20	112	0.10	<10	34	<10	6	43
S07-19414	<0.2	4.97	<5	2125	<5	0.67	<1	3	66	2	1.70	2.43	20	1.12	1637	<1	0.58	11	240	18	<5	<20	84	0.09	<10	18	<10	6	39
S07-19415	1.0	4.94	10	1240	<5	0.85	<1	16	130	138	3.16	1.86	30	1.44	2615	<1	1.06	44	400	30	<5	<20	94	0.09	<10	45	<10	7	94
S07-19416	0.6	4.81	15	1345	<5	0.72	<1	14	125	108	2.71	1.83	20	1.30	2235	<1	1.01	38	340	30	<5	<20	86	0.09	<10	43	<10	6	87
S07-19417	0.6	5.59	5	1840	<5	1.15	<1	6	114	97	2.00	2.38	10	1.21	2341	13	0.45	17	300	32	5	<20	111	0.10	<10	94	<10	7	86
S07-19418	1.0	4.56	20	1235	<5	0.96	1	15	166	41	2.94	2.08	20	1.77	2196	<1	0.69	39	440	158	<5	<20	114	0.08	<10	52	<10	6	156
S07-19419	0.4	6.00	<5	1835	<5	0.91	<1	3	152	14	1.66	2.27	20	1.13	1940	<1	1.46	10	350	26	<5	<20	134	0.10	<10	42	<10	6	49
S07-19420	0.4	5.51	5	1710	<5	0.90	<1	5	254	13	2.01	2.34	10	1.25	1506	<1	0.34	16	270	24	<5	<20	84	0.09	<10	24	<10	5	46
S07-19421	0.8	4.04	30	885	<5	1.12	<1	24	311	64	3.65	1.81	20	2.50	2361	<1	0.52	94	420	48	<5	<20	128	0.07	<10	64	<10	5	105
S07-19422	0.6	4.60	10	1310	<5	1.70	<1	9	109	65	2.05	1.80	20	1.25	3375	<1	0.87	24	500	34	<5	<20	159	0.08	<10	58	<10	7	39
S07-19423	0.4	5.08	5	1780	<5	0.59	<1	7	181	37	2.16	2.31	20	1.29	1428	<1	0.29	19	250	34	<5	<20	67	0.09	<10	22	<10	6	52
S07-19424	0.6	5.02	<5	1780	<5	0.55	<1	4	177	31	1.76	2.29	10	1.11	910	<1	0.21	11	270	28	<5	<20	65	0.10	<10	27	<10	5	28
S07-19425	0.4	5.96	20	1345	<5	1.10	<1	6	215	6	2.20	2.16	10	1.61	918	<1	0.69	35	510	26	<5	<20	122	0.11	<10	32	<10	6	54
S07-19426	0.2	4.44	45	560	<5	4.47	<1	32	474	5	4.16	2.24	<10	5.05	2394	<1	0.38	196	620	26	5	<20	428	0.06	<10	107	<10	6	64

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
S07-19427	0.4	4.40	45	615	<5	3.17	<1	27	470	2	3.20	2.06	10	4.82	1845	<1	0.37	222	510	22	5	<20	282	0.05	<10	69	<10	6	70
S07-19428	0.6	5.69	15	960	<5	0.90	<1	15	157	107	2.44	1.88	20	1.66	1252	<1	1.58	30	530	28	<5	<20	122	0.12	<10	85	<10	6	43
S07-19429	0.6	4.49	15	940	<5	1.07	<1	16	151	57	2.73	1.51	20	1.20	1695	<1	1.44	43	420	30	<5	<20	120	0.09	<10	72	<10	6	51
S07-19430	0.8	4.42	25	875	<5	0.98	<1	21	193	58	2.78	1.78	20	1.26	1692	<1	0.46	50	410	40	<5	<20	93	0.10	<10	62	<10	5	72
S07-19431	0.2	7.13	<5	475	<5	2.62	<1	9	80	38	4.41	1.17	10	1.29	729	3	3.06	25	780	28	<5	<20	355	0.33	<10	102	<10	17	43
S07-19432	0.6	3.72	15	955	<5	1.62	<1	11	190	38	2.27	1.74	10	1.20	1513	<1	0.11	34	370	46	<5	<20	170	0.07	<10	73	<10	4	51
S07-19433	0.6	6.83	25	1490	<5	1.68	<1	25	146	107	4.28	3.05	20	2.30	2552	<1	0.73	53	600	36	<5	<20	221	0.14	<10	124	<10	8	84
S07-19434	0.6	5.51	15	1215	<5	0.88	<1	21	116	52	2.95	2.40	20	1.60	2123	<1	0.64	35	450	28	<5	<20	84	0.14	<10	93	<10	6	105
S07-19435	0.6	7.26	5	1505	<5	1.08	<1	10	191	37	3.23	2.93	20	1.89	3208	<1	1.41	15	760	36	<5	<20	120	0.15	<10	85	<10	6	119
S07-19436	0.4	5.40	10	1045	<5	1.19	<1	11	160	48	2.38	1.82	10	1.79	2282	<1	1.62	36	500	30	<5	<20	129	0.10	<10	41	<10	4	56
S07-19437	0.4	6.08	<5	1570	<5	0.75	<1	6	150	42	2.33	2.71	10	1.49	1187	<1	0.56	16	300	30	<5	<20	61	0.13	<10	25	<10	5	37
S07-19438	0.6	5.29	20	1175	<5	1.85	<1	10	226	30	2.17	2.37	20	1.70	1223	<1	0.77	53	350	100	<5	<20	130	0.08	<10	47	<10	8	30
S07-19439	0.4	5.11	30	1085	<5	1.52	<1	14	248	2	1.90	2.70	20	2.94	842	<1	0.43	98	320	22	<5	<20	117	0.07	<10	42	<10	8	39
S07-19440	0.6	5.08	10	1020	<5	0.79	<1	6	125	91	1.90	2.69	20	1.97	438	<1	0.47	23	230	24	<5	<20	68	0.06	<10	25	<10	6	24
S07-19441	0.6	5.40	30	805	<5	1.34	<1	9	251	42	2.22	2.49	10	2.01	562	<1	0.57	53	390	20	<5	<20	106	0.08	<10	36	<10	6	27
S07-19442	2.0	4.98	25	340	<5	3.63	<1	22	444	57	4.09	2.25	<10	4.40	1181	<1	0.81	112	730	456	10	<20	277	0.05	<10	124	<10	5	47
S07-19443	0.4	4.04	40	70	<5	4.72	<1	53	1000	10	4.54	0.91	<10	7.90	1299	<1	0.30	414	530	18	10	<20	223	0.02	<10	117	<10	6	50
S07-19444	0.4	4.98	5	875	<5	1.74	<1	5	49	25	1.65	2.58	20	2.08	404	<1	0.43	15	220	24	<5	<20	116	0.07	<10	27	<10	7	19
S07-19445	0.4	5.18	5	1075	<5	0.80	<1	3	151	32	1.47	2.81	20	1.12	327	<1	0.38	10	210	24	<5	<20	80	0.07	<10	21	<10	7	16
S07-19446	<0.2	0.12	<5	30	<5	>10	<1	<1	3	2	0.49	0.05	<10	>10	180	<1	0.02	2	160	<2	<5	<20	109	<0.01	<10	2	<10	<1	12
S07-19447	<0.2	4.47	30	525	<5	2.29	<1	23	459	9	2.57	2.43	10	4.57	990	<1	0.24	176	370	22	<5	<20	127	0.05	<10	56	<10	7	49
S07-19448	<0.2	4.40	25	530	<5	3.63	<1	14	336	6	2.88	2.57	<10	5.01	1454	<1	0.31	86	450	18	<5	<20	262	0.05	<10	81	<10	7	47
S07-19449	0.4	5.74	35	1065	<5	3.41	<1	17	401	57	2.56	2.98	20	3.20	1543	1	0.24	103	490	32	5	<20	209	0.09	<10	68	<10	8	51
S07-19450	<0.2	3.43	50	210	<5	5.05	<1	38	601	52	3.85	1.59	<10	6.11	1984	<1	0.26	292	410	16	10	<20	204	0.04	<10	98	<10	5	60
S07-19451	0.4	4.97	60	565	<5	2.60	<1	32	524	86	3.89	2.51	10	4.60	1796	<1	0.26	211	440	20	5	<20	117	0.09	<10	134	<10	4	66
S07-19452	0.2	6.04	40	1005	<5	1.50	<1	22	347	93	2.85	3.34	20	3.12	1158	11	0.27	129	530	28	<5	<20	94	0.11	<10	106	<10	6	58
S07-19453	2.0	6.04	10	1045	<5	2.75	<1	9	142	30	1.94	3.05	20	2.29	1472	1	0.26	22	290	24	<5	<20	145	0.10	<10	50	<10	11	31
S07-19454	<0.2	4.93	40	605	<5	2.66	<1	19	375	28	2.41	2.51	10	3.27	1242	1	0.19	133	370	24	<5	<20	130	0.08	<10	67	<10	7	39
S07-19455	0.4	3.91	50	230	<5	3.13	<1	25	540	38	3.44	2.12	10	4.95	1558	<1	0.27	181	420	22	<5	<20	195	0.06	<10	87	<10	5	47
S07-19456	0.4	5.36	45	525	<5	3.89	<1	27	439	59	4.14	2.82	10	4.69	1692	3	0.37	128	570	46	<5	<20	233	0.09	<10	145	<10	7	65
S07-19457	0.2	3.07	35	115	<5	2.38	<1	19	375	18	2.30	1.45	<10	3.83	1047	<1	0.16	130	310	12	<5	<20	138	0.05	<10	54	<10	5	30
S07-19458	0.2	4.90	35	210	<5	3.45	<1	27	460	21	3.70	2.45	10	6.39	1234	<1	0.49	198	550	20	<5	<20	187	0.06	<10	91	<10	7	53
S07-19459	7.2	3.92	190	205	<5	0.39	<1	6	43	57	3.53	3.04	<10	0.26	216	6	0.66	19	410	26	60	<20	99	0.25	<10	52	<10	10	40
S07-19460	0.4	4.78	40	375	<5	2.44	<1	27	461	10	3.15	2.28	10	5.01	1246	<1	0.40	185	470	20	5	<20	139	0.06	<10	79	<10	7	38
S07-19461	0.6	4.67	30	220	<5	2.58	<1	20	249	86	3.51	2.43	10	2.79	1113	4	0.23	78	450	36	<5	<20	132	0.08	<10	88	<10	6	62
S07-19462	1.0	4.77	20	160	<5	4.54	1	14	333	73	3.03	2.42	20	2.25	1373	17	0.19	88	510	40	5	<20	202	0.08	<10	159	<10	7	127
S07-19463	1.6	6.11	25	155	<5	4.62	2	17	234	78	4.76	2.83	20	2.04	1202	25	0.25	69	940	64	15	<20	172	0.10	<10	228	<10	8	176
S07-19464	2.6	5.58	25	130	<5	3.27	2	13	145	75	4.57	2.70	20	1.64	988	32	0.18	62	840	68	15	<20	128	0.08	<10	212	<10	7	204
S07-19465	1.0	5.15	15	95	<5	3.65	2	15	215	59	4.17	2.39	20	1.68	1133	24	0.17	59	840	50	10	<20	141	0.08	<10	188	<10	6	158
S07-19466	1.6	5.14	20	130	<5	3.19	2	16	208	70	4.14	2.54	20	1.55	999	29	0.15	69	1060	52	10	<20	137	0.09	<10	229	<10	7	195

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
S07-19467	1.4	4.64	20	110	<5	3.34	1	15	160	54	3.47	2.22	20	1.62	1091	21	0.12	60	740	56	10	<20	147	0.08	<10	178	<10	7	117
S07-19468	1.4	5.02	10	110	<5	2.69	3	16	118	64	3.81	2.37	20	1.23	783	27	0.12	69	1890	54	10	<20	114	0.11	<10	286	<10	8	233
S07-19469	1.6	4.54	15	115	<5	2.65	2	14	166	60	3.96	2.20	20	1.34	795	26	0.11	63	840	54	10	<20	114	0.08	<10	204	<10	6	203
S07-19470	1.8	4.94	20	115	<5	3.90	2	16	177	82	4.25	2.37	20	1.88	1091	27	0.15	81	930	54	10	<20	152	0.08	<10	242	<10	7	194
S07-19471	1.8	4.94	20	90	<5	3.67	3	16	179	76	4.17	2.43	20	1.80	1007	27	0.16	74	920	54	10	<20	142	0.08	<10	250	<10	7	206
S07-19472	1.9	4.82	15	100	<5	3.04	3	14	189	59	3.92	2.33	20	1.47	859	26	0.11	69	790	68	10	<20	121	0.08	<10	232	<10	7	278
S07-19473	1.8	4.62	10	85	<5	3.17	2	14	156	67	3.91	2.28	20	1.51	908	26	0.13	65	910	50	10	<20	125	0.07	<10	235	<10	6	184
S07-19474	1.6	4.40	10	100	<5	3.32	3	14	194	97	3.69	2.17	20	1.50	1008	30	0.12	60	1050	46	10	<20	132	0.07	<10	241	<10	6	206
S07-19475	2.0	4.50	15	80	<5	3.17	3	14	214	94	3.94	2.17	20	1.46	1121	30	0.10	62	1100	62	10	<20	122	0.07	<10	234	<10	6	209
S07-19476	1.4	4.44	10	105	<5	2.55	2	16	135	72	3.33	2.16	20	1.13	907	19	0.13	61	1160	54	10	<20	105	0.09	<10	278	<10	6	208
S07-19477	4.6	4.40	125	250	<5	0.50	<1	10	34	669	4.95	2.42	10	1.78	370	7	0.35	23	520	98	50	<20	73	0.25	<10	55	<10	11	645
S07-19478	1.8	4.54	15	85	<5	2.48	3	14	127	102	3.62	2.18	20	1.15	883	26	0.12	67	880	64	10	<20	100	0.08	<10	253	<10	5	212
S07-19479	1.0	5.53	10	145	<5	2.89	2	12	173	40	2.98	2.60	20	1.31	930	18	0.18	44	1010	68	5	<20	121	0.10	<10	193	<10	6	165
S07-19480	2.4	5.13	20	90	<5	2.95	2	16	142	89	4.19	2.44	20	1.38	981	30	0.16	66	930	72	10	<20	112	0.09	<10	243	<10	6	189
S07-19481	2.4	3.52	15	75	<5	2.24	3	10	212	76	3.06	1.76	20	1.07	784	22	0.07	45	910	58	10	<20	118	0.06	<10	174	<10	6	210
S07-19482	2.2	5.05	20	120	<5	2.43	2	14	212	79	4.24	2.53	20	1.23	761	31	0.16	66	980	76	10	<20	110	0.08	<10	245	<10	7	198
S07-19483	2.0	4.49	20	75	<5	2.62	3	13	199	70	3.98	2.20	20	1.24	818	28	0.11	64	1070	72	10	<20	118	0.07	<10	228	<10	6	206
S07-19484	1.4	4.96	15	85	<5	2.85	2	14	231	70	3.99	2.41	20	1.39	903	25	0.17	63	990	64	10	<20	131	0.08	<10	231	<10	7	188
S07-19485	2.2	4.43	15	90	<5	2.41	2	14	136	69	3.82	2.15	20	1.33	850	26	0.15	60	790	58	10	<20	118	0.07	<10	211	<10	5	177
S07-19486	1.2	4.86	15	80	<5	2.19	2	15	199	69	3.87	2.35	20	1.26	804	30	0.18	64	830	62	10	<20	112	0.09	<10	230	<10	6	174
S07-19487	2.2	4.89	20	90	<5	2.67	2	15	197	93	4.29	2.26	20	1.46	1008	28	0.33	65	990	62	10	<20	139	0.09	<10	218	<10	6	151
S07-19488	1.2	4.17	10	105	<5	2.82	2	16	164	85	3.61	1.91	20	1.50	1045	22	0.20	64	710	50	10	<20	143	0.08	<10	195	<10	5	185
S07-19489	1.4	4.58	15	115	<5	2.18	3	15	185	94	4.06	2.17	20	1.22	758	29	0.23	63	910	58	10	<20	123	0.08	<10	247	<10	6	265
S07-19490	0.2	6.37	10	120	<5	4.14	1	15	200	100	3.73	2.64	20	1.84	1001	16	0.93	40	970	44	<5	<20	218	0.13	<10	225	<10	7	134
S07-19491	0.2	6.04	15	130	<5	4.40	1	18	133	129	4.03	2.92	10	2.28	904	9	0.81	27	750	40	<5	<20	266	0.11	<10	239	<10	8	114
S07-19492	0.4	6.16	15	155	<5	3.89	3	11	165	223	3.41	2.60	20	1.75	849	14	0.35	31	900	114	<5	<20	225	0.12	<10	214	<10	9	231
S07-19493	1.4	6.23	10	920	<5	2.67	<1	7	217	70	2.27	2.95	20	1.49	536	3	0.76	13	570	28	<5	<20	153	0.10	<10	86	<10	9	55
S07-19494	0.2	7.38	15	1100	<5	3.15	<1	7	177	76	2.40	3.02	30	1.59	672	2	0.86	14	700	34	<5	<20	153	0.13	<10	93	<10	10	44
S07-19495	<0.2	4.98	10	610	<5	2.96	1	8	243	67	2.21	1.90	10	1.31	706	2	1.15	15	520	24	<5	<20	151	0.10	<10	84	<10	6	102
S07-19496	<0.2	7.18	10	825	<5	4.26	<1	8	149	68	2.39	2.64	20	1.84	994	<1	2.15	11	700	30	<5	<20	206	0.12	<10	104	<10	7	78
S07-19497	0.2	6.65	10	640	<5	3.13	<1	7	152	50	2.39	2.32	20	1.58	755	1	2.14	9	510	24	<5	<20	221	0.11	<10	71	<10	9	33
S07-19498	<0.2	6.97	10	770	<5	2.98	<1	7	104	36	2.41	3.05	20	1.66	668	6	1.73	9	560	24	<5	<20	215	0.12	<10	85	<10	9	38
S07-19499	<0.2	0.14	<5	45	<5	>10	<1	<1	<1	3	0.52	0.05	<10	>10	180	<1	0.04	2	190	2	<5	<20	112	<0.01	<10	3	<10	<1	10
S07-19500	<0.2	6.82	10	610	<5	3.12	<1	7	115	34	2.22	3.15	20	1.71	672	3	1.76	8	470	26	<5	<20	209	0.10	<10	80	<10	8	39
S07-19501	<0.2	7.00	10	1240	<5	3.40	<1	7	132	36	2.39	2.99	20	1.66	747	3	1.49	9	660	28	<5	<20	198	0.12	<10	76	<10	9	45
S07-19502	<0.2	6.18	5	800	<5	2.88	<1	7	140	46	2.38	2.24	20	1.34	698	<1	2.12	11	410	26	<5	<20	176	0.09	<10	60	<10	7	38
S07-19503	<0.2	6.75	<5	1165	<5	3.30	<1	6	102	44	2.31	3.10	20	1.65	736	2	1.47	9	470	26	<5	<20	180	0.10	<10	79	<10	8	46
S07-19504	<0.2	4.94	5	415	<5	2.91	1	10	122	75	2.40	1.78	20	1.23	725	3	1.62	23	460	22	<5	<20	152	0.11	<10	136	<10	5	104
S07-19505	0.2	6.12	10	185	<5	3.60	<1	12	146	103	3.03	1.90	20	1.31	1060	6	2.62	22	1000	30	<5	<20	189	0.13	<10	157	<10	6	87
S07-19506	1.0	6.80	15	335	<5	3.23	<1	10	141	132	2.76	2.21	20	1.32	855	6	2.91	26	730	36	<5	<20	177	0.16	<10	192	<10	5	62

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
S07-19507	0.6	7.09	25	100	<5	3.08	2	14	147	108	3.48	2.21	10	1.12	973	12	2.25	40	950	40	<5	<20	178	0.14	<10	287	<10	5	169
S07-19508	0.2	5.46	40	150	<5	2.79	2	26	155	75	6.05	1.76	10	0.98	776	36	1.09	52	650	40	<5	<20	125	0.09	<10	237	<10	4	198
S07-19509	<0.2	5.80	10	850	<5	3.78	<1	6	138	30	2.17	1.88	20	1.30	956	5	1.15	17	620	30	<5	<20	174	0.12	<10	84	<10	6	77
S07-19510	<0.2	5.51	15	905	<5	3.34	<1	8	129	41	2.23	2.13	10	1.22	815	3	0.44	11	440	30	<5	<20	138	0.10	<10	69	<10	5	64
S07-19511	<0.2	6.36	15	590	<5	2.86	<1	10	231	74	2.71	2.42	20	1.14	893	3	1.11	14	720	36	<5	<20	156	0.14	<10	97	<10	6	73
S07-19512	<0.2	5.49	10	985	<5	4.91	1	5	241	86	2.94	2.39	20	1.70	1415	<1	0.27	12	1000	46	<5	<20	229	0.12	<10	80	<10	8	131
S07-19513	0.8	7.18	20	280	<5	4.65	<1	17	178	64	4.20	2.21	10	1.95	1345	<1	0.57	26	670	46	<5	<20	250	0.17	<10	127	<10	7	103
S07-19514	<0.2	6.19	10	1035	<5	3.00	<1	13	175	50	3.83	2.45	10	1.75	1131	<1	0.89	17	1020	36	<5	<20	172	0.16	<10	117	<10	6	96
S07-19515	<0.2	6.92	15	990	<5	3.53	<1	15	86	36	4.00	2.76	20	1.97	1421	<1	1.06	13	1300	34	<5	<20	197	0.18	<10	113	<10	6	104
S07-19516	<0.2	6.82	10	940	<5	3.39	<1	14	155	34	3.92	2.41	20	1.97	1514	<1	1.00	15	1360	34	<5	<20	197	0.20	<10	111	<10	7	120
S07-19517	<0.2	6.98	10	735	<5	3.67	<1	14	101	38	3.52	2.60	20	1.88	1264	<1	1.32	12	1070	34	<5	<20	214	0.17	<10	120	<10	5	105
S07-19518	<0.2	7.40	20	665	<5	4.47	<1	17	145	93	3.79	2.37	10	1.85	1111	1	1.72	20	860	40	<5	<20	226	0.16	<10	168	<10	6	88
S07-19519	<0.2	7.40	15	685	<5	4.59	<1	19	163	71	4.33	2.43	10	2.01	1253	4	1.29	20	910	42	<5	<20	219	0.16	<10	176	<10	6	99
S07-19520	<0.2	7.57	10	625	<5	3.92	<1	19	98	40	4.09	2.57	10	1.89	1159	<1	2.03	17	950	34	<5	<20	247	0.20	<10	181	<10	5	100
S07-19521	<0.2	6.16	15	670	<5	3.89	<1	9	140	55	3.19	2.32	10	1.23	928	<1	1.42	15	610	32	<5	<20	218	0.13	<10	112	<10	5	86
S07-19522	<0.2	6.01	15	970	<5	2.98	<1	8	136	50	2.38	2.56	20	1.02	740	6	1.45	13	570	28	<5	<20	193	0.14	<10	105	<10	6	82
S07-19523	<0.2	6.61	25	505	<5	3.04	1	11	185	52	2.76	2.31	20	0.89	739	30	1.71	20	740	26	<5	<20	197	0.14	<10	164	<10	7	105
S07-19524	<0.2	7.42	20	990	<5	3.36	<1	10	154	59	3.08	2.32	30	0.97	867	17	1.40	13	820	32	<5	<20	194	0.16	<10	91	<10	8	81
S07-19525	<0.2	6.22	10	805	<5	3.01	2	8	246	51	2.42	2.19	20	0.83	828	21	1.55	19	630	26	<5	<20	199	0.16	<10	142	<10	6	124
S07-19526	<0.2	0.12	<5	35	<5	>10	<1	<1	1	<1	0.49	0.03	<10	>10	179	<1	0.02	2	180	<2	<5	<20	100	<0.01	<10	1	<10	<1	15
S07-19527	<0.2	7.78	15	1145	<5	3.21	<1	8	102	56	3.07	2.56	30	1.06	905	8	1.16	9	810	32	<5	<20	201	0.16	<10	57	<10	9	71
S07-19528	<0.2	7.35	10	595	<5	3.19	<1	15	124	67	3.79	2.21	20	1.64	1128	3	1.77	23	790	32	<5	<20	267	0.17	<10	157	<10	6	89
S07-19529	<0.2	7.61	15	295	<5	2.91	<1	14	107	64	3.82	1.50	10	1.58	1169	<1	4.37	21	540	36	<5	<20	314	0.14	<10	169	<10	3	79
S07-19530	<0.2	8.21	15	375	<5	3.04	<1	18	69	52	4.29	1.93	10	1.83	1318	<1	3.92	24	890	32	<5	<20	298	0.15	<10	180	<10	4	94
S07-19531	<0.2	8.00	10	875	<5	3.35	<1	17	64	58	4.67	2.00	10	1.94	1283	<1	3.23	22	720	30	<5	<20	294	0.16	<10	182	<10	5	82
S07-19532	<0.2	7.29	10	565	<5	4.57	<1	15	81	73	3.70	2.25	<10	1.69	1208	<1	2.13	17	660	30	<5	<20	365	0.17	<10	180	<10	5	51
S07-19533	<0.2	7.51	15	815	<5	4.36	<1	12	103	72	3.56	2.40	20	1.45	1084	<1	1.44	13	1010	36	<5	<20	386	0.15	<10	112	<10	7	41
S07-19534	0.8	5.91	125	220	<5	0.25	<1	8	25	30	3.26	4.19	10	0.30	175	3	0.11	16	500	24	35	<20	55	0.38	<10	71	<10	11	60
S07-19535	0.4	7.65	30	425	<5	4.87	<1	23	90	179	5.92	2.74	20	1.71	1321	<1	1.86	16	1860	40	<5	<20	441	0.28	<10	225	<10	11	68
S07-19536	0.6	7.10	35	325	<5	4.82	<1	19	147	157	4.96	2.76	20	1.56	1204	<1	1.54	13	1890	40	<5	<20	428	0.23	<10	200	<10	11	48
S07-19537	0.6	8.09	15	515	<5	5.20	<1	18	122	180	5.19	2.87	20	1.58	1237	<1	1.79	14	1930	38	<5	<20	405	0.25	<10	212	<10	11	74
S07-19538	0.4	7.42	5	405	<5	4.16	<1	16	58	187	4.84	2.43	20	1.65	1131	<1	2.69	12	1850	32	<5	<20	336	0.25	<10	207	<10	10	77
S07-19539	0.6	5.83	20	355	<5	3.48	<1	18	181	143	4.93	1.89	20	1.30	1075	<1	1.79	12	1550	36	<5	<20	331	0.21	<10	172	<10	9	44
S07-19540	0.4	7.06	10	590	<5	4.20	<1	15	93	165	4.54	2.33	20	1.81	1306	<1	2.51	12	1490	44	<5	<20	442	0.22	<10	188	<10	11	64
S07-19541	<0.2	7.51	5	870	<5	3.18	<1	12	88	50	3.97	2.60	20	1.78	970	<1	2.52	16	770	30	<5	<20	346	0.18	<10	130	<10	7	73
S07-19542	1.4	8.68	10	875	<5	4.44	4	15	201	173	4.70	2.88	20	1.75	1306	<1	2.37	19	1100	56	<5	<20	404	0.21	<10	166	<10	8	332
S07-19543	2.2	8.12	10	855	<5	4.03	1	16	102	841	4.55	2.75	20	1.75	1179	<1	2.14	18	960	94	<5	<20	394	0.19	<10	163	<10	6	133
S07-19544	<0.2	7.56	15	770	<5	3.82	<1	15	248	68	4.43	2.40	10	1.76	1100	<1	2.08	22	1100	42	<5	<20	364	0.20	<10	166	<10	7	63
S07-19545	2.0	7.52	5	585	<5	4.25	<1	13	155	49	4.08	2.72	10	1.50	1279	<1	1.81	14	880	34	<5	<20	287	0.18	<10	124	<10	6	89
S07-19546	<0.2	7.79	10	715	<5	3.97	<1	11	124	84	3.38	3.14	20	1.39	998	<1	1.81	11	590	32	<5	<20	289	0.18	<10	107	<10	6	49


Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
S07-19547	0.2	6.75	5	560	<5	3.26	<1	12	128	60	3.16	2.32	20	1.32	813	<1	3.21	14	470	26	<5	<20	314	0.17	<10	120	<10	5	57
S07-19548	0.2	8.58	10	785	<5	4.65	<1	18	109	102	4.60	2.64	10	1.79	1246	<1	3.18	20	730	34	<5	<20	451	0.21	<10	178	<10	5	75
S07-19549	3.6	5.80	25	105	<5	4.20	60	26	243	588	5.25	1.61	<10	1.37	1154	2	2.19	29	1200	266	<5	<20	493	0.13	<10	128	<10	6	4030
S07-19550	<0.2	7.86	10	575	<5	3.13	<1	17	133	56	4.16	1.75	10	1.61	1022	<1	4.15	17	810	32	<5	<20	511	0.22	<10	150	<10	5	76
S07-19551	<0.2	8.12	10	505	<5	3.04	<1	17	74	61	4.67	1.91	<10	1.68	1033	<1	4.41	16	810	32	<5	<20	493	0.22	<10	168	<10	4	75
S07-19552	0.2	8.11	20	545	<5	3.64	<1	25	132	90	4.89	1.91	10	2.22	1114	<1	3.53	39	810	40	<5	<20	480	0.24	<10	202	<10	5	82
S07-19553	<0.2	7.74	20	615	<5	4.75	<1	28	214	47	5.24	2.13	10	3.12	1313	<1	2.83	53	1000	28	<5	<20	518	0.21	<10	233	<10	6	73
S07-19554	<0.2	7.63	15	630	<5	3.91	<1	26	181	35	4.91	2.12	10	3.17	1102	<1	2.47	49	930	30	<5	<20	411	0.21	<10	231	<10	7	76
S07-19555	<0.2	0.11	<5	15	<5	>10	<1	<1	2	2	0.55	0.04	<10	>10	184	<1	0.05	3	170	2	<5	<20	78	<0.01	<10	2	<10	<1	20
S07-19556	<0.2	7.49	10	450	<5	3.63	<1	22	159	50	4.74	1.62	10	2.60	1044	<1	3.21	34	970	34	<5	<20	437	0.22	<10	203	<10	7	58
S07-19557	<0.2	7.91	15	495	<5	4.08	<1	25	149	108	5.04	1.48	10	3.01	1066	<1	3.48	39	950	32	<5	<20	458	0.21	<10	212	<10	7	70
S07-19558	<0.2	7.43	15	625	<5	4.56	<1	26	160	75	4.89	1.95	10	3.08	1168	<1	2.95	47	860	30	<5	<20	470	0.19	<10	212	<10	6	57
S07-19559	<0.2	7.66	10	200	<5	5.24	<1	25	107	48	4.97	0.66	10	3.06	1166	<1	3.93	41	1080	32	<5	<20	455	0.27	<10	224	<10	9	56
S07-19560	<0.2	7.91	5	390	<5	4.73	<1	24	105	86	5.11	1.49	10	3.40	1198	<1	3.10	36	1090	34	<5	<20	443	0.22	<10	245	<10	7	74
S07-19561	<0.2	8.23	10	615	<5	4.35	<1	25	70	92	4.98	2.14	10	3.26	1197	<1	3.01	30	780	32	<5	<20	452	0.19	<10	253	<10	6	64
S07-19562	<0.2	7.17	10	640	<5	4.01	<1	22	105	81	4.63	2.22	<10	2.88	1126	<1	2.64	24	770	40	<5	<20	510	0.22	<10	239	<10	7	59
S07-19563	<0.2	8.55	15	640	<5	2.98	<1	29	79	111	5.10	2.10	10	2.44	1145	<1	3.91	28	920	36	<5	<20	476	0.29	<10	259	<10	6	53
S07-19564	<0.2	8.04	10	720	<5	3.59	<1	22	99	102	4.99	1.67	10	2.58	1050	<1	3.88	31	960	32	<5	<20	450	0.32	<10	350	<10	7	73
S07-19565	7.1	3.90	240	195	<5	0.40	<1	7	47	53	3.64	2.92	<10	0.25	236	6	0.60	24	420	26	65	<20	104	0.29	<10	53	<10	10	53
S07-19566	<0.2	8.19	15	660	<5	3.31	<1	27	135	63	5.25	1.11	10	3.53	1310	<1	3.69	56	970	34	<5	<20	375	0.36	<10	259	<10	11	72
S07-19567	<0.2	8.18	15	340	<5	2.86	<1	27	110	105	5.13	0.84	10	3.99	1299	<1	3.91	55	1060	34	<5	<20	348	0.49	<10	293	<10	16	73
S07-19568	<0.2	8.72	25	345	<5	3.18	<1	29	99	104	5.48	0.84	10	4.16	1391	<1	3.99	57	1120	34	<5	<20	362	0.43	<10	290	<10	15	71
S07-19569	<0.2	8.10	15	285	<5	4.23	<1	24	72	106	5.16	0.87	10	3.88	1379	<1	3.96	47	1190	32	<5	<20	470	0.34	<10	271	<10	12	68
S07-19570	<0.2	8.65	15	90	<5	2.97	<1	29	85	119	5.32	0.35	10	3.72	1269	<1	4.64	49	1210	34	<5	<20	412	0.36	<10	266	<10	10	71
S07-19571	<0.2	7.44	15	90	<5	3.65	<1	30	223	73	5.33	0.32	10	3.91	1189	<1	4.18	90	1160	32	<5	<20	514	0.20	<10	246	<10	9	69
S07-19572	<0.2	7.24	25	160	<5	4.31	<1	37	279	286	5.33	0.32	10	4.64	1216	<1	4.07	122	1220	38	<5	<20	567	0.14	<10	337	<10	9	71
S07-19573	<0.2	7.17	30	140	<5	4.15	<1	37	370	154	5.41	0.30	10	5.69	1355	<1	3.45	148	1120	30	<5	<20	540	0.11	<10	286	<10	8	70
S07-19574	<0.2	6.98	20	370	<5	4.42	<1	32	289	74	5.25	0.59	10	5.06	1227	<1	3.52	108	1170	34	<5	<20	531	0.12	<10	224	<10	8	65
S07-19575	<0.2	7.30	30	215	<5	4.71	<1	39	388	79	5.47	0.41	20	5.01	1265	<1	3.69	144	1540	32	<5	<20	542	0.15	<10	235	<10	9	67
S07-19576	<0.2	7.30	20	615	<5	4.55	<1	34	278	99	5.35	1.02	10	5.31	1397	<1	3.14	104	1370	34	<5	<20	542	0.12	<10	255	<10	8	63
S07-19577	<0.2	7.41	10	1260	<5	3.36	<1	25	132	92	5.03	2.15	10	4.33	1216	<1	3.50	53	1010	28	<5	<20	462	0.17	<10	257	<10	7	60
S07-19578	<0.2	8.38	10	1575	<5	3.44	<1	23	78	84	4.76	2.69	10	3.40	1290	<1	3.23	36	1110	32	<5	<20	484	0.22	<10	237	<10	8	55
S07-19579	<0.2	8.91	10	1620	<5	3.96	<1	21	76	40	5.04	3.04	10	2.98	1439	<1	2.81	32	1170	34	<5	<20	500	0.24	<10	237	<10	7	47
S07-19580	<0.2	7.04	10	1680	<5	4.12	<1	25	99	74	4.08	2.62	10	3.26	1392	<1	2.41	34	1010	30	<5	<20	637	0.21	<10	233	<10	8	49
S07-19581	<0.2	0.07	<5	15	<5	>10	<1	2	<1	<1	0.50	0.03	<10	>10	174	<1	0.02	2	170	<2	<5	<20	76	<0.01	<10	3	<10	<1	19
S07-19582	<0.2	7.60	15	1330	<5	3.95	<1	22	79	80	4.65	2.68	10	3.16	1439	<1	2.67	40	1050	32	<5	<20	522	0.23	<10	240	<10	7	64
S07-19583	<0.2	7.24	10	1520	<5	5.50	<1	14	95	21	4.56	2.88	10	3.00	1566	<1	2.08	27	1080	34	<5	<20	617	0.19	<10	201	<10	8	40
S07-19584	<0.2	7.14	10	2095	<5	5.18	<1	18	86	68	4.47	2.64	10	2.95	1422	<1	2.44	28	1160	34	<5	<20	643	0.20	<10	195	<10	10	53
S07-19585	<0.2	7.64	5	2285	<5	2.62	<1	20	62	94	4.63	2.18	20	2.65	1330	<1	3.12	23	1380	36	<5	<20	427	0.27	<10	203	<10	8	73
S07-19586	<0.2	7.41	5	1670	<5	2.40	<1	21	39	76	5.45	1.53	20	2.29	1514	<1	4.32	17	1560	32	<5	<20	452	0.31	<10	185	<10	7	90


Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
S07-19587	<0.2	7.67	5	2600	<5	1.78	<1	15	39	40	4.61	1.74	20	2.13	1386	<1	3.93	15	1240	32	<5	<20	366	0.26	<10	150	<10	9	80
S07-19588	<0.2	7.47	10	2865	<5	1.29	<1	11	61	78	4.33	1.69	20	1.86	1248	<1	3.89	12	2270	40	<5	<20	312	0.28	<10	103	<10	10	86
S07-19589	0.2	6.51	5	3330	<5	1.13	<1	11	45	78	4.10	1.73	20	1.83	1195	<1	4.08	11	1920	36	<5	<20	282	0.28	<10	108	<10	7	88
S07-19590	0.2	7.44	5	3185	<5	1.82	<1	15	88	20	4.65	2.42	20	2.32	1413	<1	2.69	17	1400	42	<5	<20	346	0.24	<10	154	<10	7	79
S07-19591	<0.2	6.90	10	2950	<5	2.49	<1	18	83	41	4.19	2.04	10	2.70	1339	<1	3.04	25	1050	36	<5	<20	471	0.24	<10	187	<10	7	58
S07-19592	<0.2	6.90	10	1665	<5	2.04	<1	22	71	73	4.79	2.18	10	3.52	1526	<1	2.82	34	1030	30	<5	<20	338	0.23	<10	212	<10	5	72
S07-19593	0.2	7.20	10	1415	<5	3.85	<1	21	60	80	4.48	1.79	10	3.26	2083	<1	3.50	33	1140	32	<5	<20	509	0.21	<10	196	<10	7	61
S07-19594	0.2	7.24	5	1525	<5	3.12	<1	18	51	84	3.99	1.99	10	2.97	1477	<1	3.43	29	860	32	<5	<20	422	0.21	<10	200	<10	6	71
S07-19595	<0.2	6.95	10	1620	<5	4.27	<1	20	86	47	4.57	2.34	10	2.88	1756	<1	2.14	32	950	36	<5	<20	481	0.20	<10	174	<10	7	68
S07-19596	0.2	6.75	15	1855	<5	3.97	<1	21	79	72	4.26	2.78	10	2.78	1649	2	0.96	31	1140	38	<5	<20	418	0.20	<10	162	<10	8	114
S07-19597	0.2	6.27	25	990	<5	1.78	1	15	130	73	4.10	2.65	20	2.13	1311	12	0.22	55	710	34	<5	<20	195	0.16	<10	183	<10	6	211
S07-19598	<0.2	5.89	35	1655	<5	2.57	1	14	156	88	2.73	2.70	20	1.91	2293	4	0.18	111	530	34	<5	<20	268	0.16	<10	118	<10	6	213
S07-19599	0.2	4.18	25	1040	<5	2.51	<1	9	170	28	2.39	2.03	20	1.70	2728	<1	0.10	95	400	24	<5	<20	276	0.15	<10	72	<10	5	94
S07-19600	0.8	4.72	30	1155	<5	2.35	<1	14	126	90	2.58	2.22	20	1.68	3142	<1	0.12	94	360	30	<5	<20	248	0.19	<10	79	<10	6	115
S07-19601	0.6	5.46	60	320	<5	1.45	<1	20	145	108	3.31	2.58	20	1.54	2686	<1	0.18	185	450	36	<5	<20	166	0.19	<10	90	<10	5	129
S07-19602	0.6	5.64	45	1355	<5	1.16	<1	17	99	116	2.64	2.75	20	1.63	4356	<1	0.24	171	400	40	<5	<20	142	0.18	<10	94	<10	5	158
S07-19603	0.8	5.77	60	505	<5	1.06	<1	26	122	150	2.79	2.74	20	1.60	3958	<1	0.35	236	430	36	<5	<20	134	0.19	<10	102	<10	5	184
S07-19604	4.8	4.61	120	285	<5	0.53	<1	12	34	563	4.95	2.55	10	1.78	404	7	0.31	26	530	118	50	<20	77	0.29	<10	53	<10	11	641
S07-19605	0.6	5.27	45	575	<5	1.30	<1	20	154	105	3.07	2.66	20	1.70	4257	<1	0.34	152	390	38	<5	<20	173	0.16	<10	94	<10	4	134
S07-19606	0.4	5.44	45	1160	<5	1.32	<1	15	133	82	2.57	2.55	20	1.62	5843	<1	0.49	175	420	34	<5	<20	160	0.15	<10	91	<10	4	108
S07-19607	0.4	5.13	45	1180	<5	1.24	<1	16	121	103	2.79	2.58	20	1.82	5846	<1	0.43	186	380	38	<5	<20	163	0.16	<10	99	<10	5	179
S07-19608	<0.2	6.40	40	1335	<5	1.35	<1	13	174	78	3.01	2.99	30	1.70	5135	<1	0.36	151	490	38	<5	<20	154	0.21	<10	98	<10	5	120
S07-19609	0.4	5.77	55	1090	<5	2.90	<1	17	220	104	3.20	2.57	20	1.78	6821	<1	0.22	169	450	56	<5	<20	297	0.19	<10	94	<10	7	166
S07-19610	0.4	6.12	65	1065	<5	1.75	1	21	189	151	3.44	2.69	20	1.76	6448	<1	0.28	225	500	44	<5	<20	187	0.19	<10	98	<10	6	283
S07-19611	0.2	5.68	45	1175	<5	1.70	<1	13	148	132	2.86	2.84	30	1.82	6134	<1	0.38	165	380	36	<5	<20	204	0.17	<10	104	<10	5	182
S07-19612	0.3	5.04	45	1205	<5	0.95	<1	18	159	80	2.54	2.82	20	1.71	4223	<1	0.44	157	510	32	<5	<20	147	0.19	<10	104	<10	4	97
S07-19613	0.2	5.28	45	1250	<5	1.04	<1	18	140	75	2.55	2.95	20	1.76	4380	<1	0.48	167	570	32	<5	<20	154	0.18	<10	105	<10	4	99
S07-19614	0.4	4.98	45	735	<5	1.20	<1	13	196	84	2.86	2.77	20	1.73	4141	<1	0.38	156	430	36	<5	<20	169	0.16	<10	105	<10	4	160
S07-19615	0.6	4.92	55	180	<5	1.25	<1	23	231	109	3.80	2.62	20	1.66	4190	<1	0.36	174	410	48	<5	<20	165	0.16	<10	96	<10	5	154
S07-19616	0.4	4.60	60	415	<5	0.83	<1	20	141	189	2.56	2.89	20	1.56	3243	2	0.48	224	390	36	<5	<20	138	0.16	<10	114	<10	4	243
S07-19617	0.4	5.10	60	1225	<5	0.90	<1	18	171	145	2.76	2.57	20	1.67	3139	<1	0.46	164	680	40	<5	<20	146	0.16	<10	105	<10	5	182
S07-19402	0.6	5.06	50	700	<5	1.05	<1	21	109	61	3.02	2.13	20	1.04	1703	<1	0.72	54	550	30	<5	<20	97	0.17	<10	115	<10	8	60
S07-19411	0.2	2.76	20	555	<5	3.13	<1	13	201	22	3.01	1.28	20	2.42	2864	<1	0.11	43	310	16	<5	<20	252	0.05	<10	65	<10	8	60
S07-19420	0.4	5.34	<5	1745	<5	0.91	<1	5	267	13	1.92	2.38	10	1.27	1435	<1	0.34	15	250	24	<5	<20	84	0.09	<10	23	<10	6	40
S07-19437	0.4	5.54	<5	1540	<5	0.69	<1	5	143	41	2.24	2.68	10	1.46	1162	<1	0.55	15	260	24	<5	<20	60	0.11	<10	24	<10	5	35
S07-19447	0.4	4.39	30	515	<5	2.25	<1	23	454	8	2.49	2.24	10	4.35	952	<1	0.24	176	350	20	<5	<20	116	0.05	<10	51	<10	7	51
S07-19455	3.0	4.06	55	240	<5	3.33	<1	27	518	40	3.66	2.13	10	5.11	1619	<1	0.28	191	440	20	5	<20	203	0.07	<10	89	<10	5	54
S07-19472	2.2	4.67	15	100	<5	2.91	3	14	181	56	3.77	2.25	20	1.44	827	25	0.12	67	760	64	10	<20	120	0.08	<10	223	<10	6	266
S07-19481	2.2	3.65	10	80	<5	2.40	3	9	216	78	2.93	1.76	20	1.09	830	22	0.07	46	940	60	15	<20	119	0.06	<10	176	<10	6	213
S07-19490	0.4	6.17	5	115	<5	3.96	1	15	201	103	3.83	2.67	20	1.77	921	15	0.96	37	920	42	<5	<20	212	0.11	<10	224	<10	8	130
S07-19507	0.8	6.76	25	115	<5	2.88	2	14	140	104	3.33	2.16	10	1.08	963	12	2.18	40	920	40	<5	<20	175	0.13	<10	283	<10	5	163

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
S07-19516	<0.2	6.95	10	905	<5	3.45	<1	14	153	35	4.07	2.37	20	1.88	1407	<1	1.04	14	1260	30	<5	<20	188	0.18	<10	110	<10	7	115
S07-19525	<0.2	6.31	10	815	<5	2.98	2	8	262	51	2.51	2.18	20	0.84	812	21	1.54	19	620	24	<5	<20	198	0.15	<10	143	<10	6	121
S07-19542	1.0	8.56	10	880	<5	4.35	4	14	203	175	4.68	2.76	20	1.76	1294	<1	2.26	17	1080	50	<5	<20	402	0.20	<10	167	<10	6	328
S07-19551	<0.2	8.13	10	500	<5	2.96	<1	17	85	61	4.65	1.90	<10	1.66	1016	<1	4.33	16	790	34	<5	<20	491	0.20	<10	166	<10	4	75
S07-19560	<0.2	8.35	10	395	<5	4.82	<1	24	104	89	5.45	1.54	10	3.50	1272	<1	3.28	38	1160	34	<5	<20	456	0.25	<10	250	<10	7	75
S07-19577	<0.2	7.49	10	1285	<5	3.49	<1	26	137	90	5.06	2.19	10	4.44	1252	<1	3.45	53	1040	32	<5	<20	477	0.16	<10	260	<10	7	60
S07-19586	0.2	7.09	5	1645	<5	2.55	<1	19	39	71	5.25	1.46	20	2.27	1494	<1	4.26	17	1530	32	<5	<20	444	0.30	<10	180	<10	7	94
S07-19595	<0.2	6.77	10	1640	<5	4.15	<1	19	90	49	4.38	2.35	10	2.94	1681	<1	2.11	33	900	32	<5	<20	487	0.19	<10	174	<10	7	66
S07-19612	0.4	5.29	65	1265	<5	1.02	<1	18	162	81	2.61	2.95	30	1.75	4442	<1	0.46	162	530	36	<5	<20	149	0.20	<10	106	<10	4	103
t:																													
S07-19402	0.4	5.14	45	700	<5	0.89	<1	21	112	67	2.82	2.11	20	1.07	1824	<1	0.72	44	590	26	<5	<20	95	0.16	<10	120	<10	7	55
S07-19437	0.5	5.82	<5	1540	<5	0.80	<1	7	140	43	2.45	2.71	10	1.54	1213	<1	0.60	20	300	28	<5	<20	65	0.13	<10	27	<10	6	40
S07-19472	2.2	4.95	15	110	<5	2.97	4	14	205	60	3.93	2.44	20	1.35	858	27	0.12	68	790	64	10	<20	112	0.09	<10	244	<10	7	277
S07-19507	1.0	6.58	25	120	<5	2.97	1	17	160	104	3.68	2.10	20	1.10	942	11	2.25	40	870	46	<5	<20	163	0.13	<10	261	<10	6	166
S07-19542	0.9	8.64	10	890	<5	4.30	4	17	194	171	4.61	2.92	20	1.79	1190	<1	2.25	19	1080	48	<5	<20	404	0.22	<10	175	<10	6	309
S07-19577	<0.2	7.51	15	1265	<5	3.66	<1	26	134	93	4.86	2.13	10	4.40	1221	<1	3.42	54	1020	30	<5	<20	478	0.17	<10	257	<10	7	62
S07-19612	0.4	4.84	50	1160	<5	0.98	<1	16	170	91	2.53	2.94	30	1.65	4216	<1	0.51	157	450	32	<5	<20	155	0.19	<10	103	<10	4	107
ard:																													
}	0.5	5.62	20	1245	<5	2.29	<1	14	54	36	3.95	1.45	40	1.31	2438	5	1.19	29	1630	56	<5	<20	258	0.28	<10	109	<10	28	195
}	0.5	5.41	20	1235	<5	2.34	<1	14	56	36	4.21	1.41	40	1.33	2484	4	1.11	28	1710	56	<5	<20	269	0.28	<10	109	<10	28	193
}	0.4	5.74	20	1235	<5	2.45	<1	14	54	37	4.12	1.46	40	1.31	2582	5	1.19	27	1720	54	<5	<20	253	0.29	<10	111	<10	28	208
}	0.4	5.39	20	1295	<5	2.51	<1	14	56	33	4.02	1.44	40	1.30	2549	4	1.20	32	1720	62	<5	<20	243	0.31	<10	106	<10	28	203
}	0.5	5.40	25	1225	<5	2.24	<1	14	58	34	4.09	1.45	40	1.32	2434	4	1.12	31	1730	54	<5	<20	260	0.32	<10	118	<10	29	212
}	0.4	5.74	25	1240	<5	2.52	<1	14	58	34	4.12	1.42	40	1.30	2495	5	1.12	33	1610	62	<5	<20	270	0.34	<10	118	<10	28	207
}	0.4	5.71	20	1220	<5	2.40	<1	14	56	35	4.15	1.41	30	1.34	2516	4	1.19	33	1730	58	<5	<20	264	0.31	<10	109	<10	26	211

ACID DIGEST/ICP-FINISH
ACID DIGEST/AA-FINISH

3s/td2298bs


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2297

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

17-Mar-08

Attention: Bob Singh

No. of samples received: 201
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-160
Samples submitted by: Tasha Gainer

Metallic Assays


ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-34739	<0.03	<0.001
2	S07-34740	<0.03	<0.001
3	S07-34741	<0.03	<0.001
4	S07-34742	<0.03	<0.001
5	S07-34743	<0.03	<0.001
6	S07-34744	<0.03	<0.001
7	S07-34745	<0.03	<0.001
8	S07-34746	<0.03	<0.001
9	S07-34747	<0.03	<0.001
10	S07-34748	<0.03	<0.001
11	S07-34749	<0.03	<0.001
12	S07-34750	<0.03	<0.001
13	S07-34751	<0.03	<0.001
14	S07-34752	<0.03	<0.001
15	S07-34753	<0.03	<0.001
16	S07-34754	<0.03	<0.001
17	S07-34755	0.03	0.001
18	S07-34756	<0.03	<0.001
19	S07-34757	<0.03	<0.001
20	S07-34758	<0.03	<0.001
21	S07-34759	<0.03	<0.001
22	S07-34760	<0.03	<0.001
23	S07-34761	<0.03	<0.001
24	S07-34762	<0.03	<0.001
25	S07-34763	<0.03	<0.001
26	S07-34764	6.66	0.194
27	S07-34765	<0.03	<0.001
28	S07-34766	<0.03	<0.001

Jutta Jealouse
ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	S07-34767	<0.03	<0.001
30	S07-34768	0.08	0.002
31	S07-34769	0.04	0.001
32	S07-34770	<0.03	<0.001
33	S07-34771	<0.03	<0.001
34	S07-34772	<0.03	<0.001
35	S07-34773	<0.03	<0.001
36	S07-34774	<0.03	<0.001
37	S07-34775	<0.03	<0.001
38	S07-34776	<0.03	<0.001
39	S07-34777	<0.03	<0.001
40	S07-34778	<0.03	<0.001
41	S07-34779	* <0.03	<0.001
42	S07-34780	<0.03	<0.001
43	S07-34781	<0.03	<0.001
44	S07-34782	<0.03	<0.001
45	S07-34783	<0.03	<0.001
46	S07-34784	<0.03	<0.001
47	S07-34785	<0.03	<0.001
48	S07-34786	<0.03	<0.001
49	S07-34787	<0.03	<0.001
50	S07-34788	* 0.41	0.012
51	S07-34789	<0.03	<0.001
52	S07-34790	0.09	0.002
53	S07-34791	<0.03	<0.001
54	S07-34792	<0.03	<0.001
55	S07-34793	<0.03	<0.001
56	S07-34794	<0.03	<0.001
57	S07-34795	0.13	0.004
58	S07-34796	0.50	0.015
59	S07-34797	0.74	0.022
60	S07-34798	0.11	0.003
61	S07-34799	0.15	0.004
62	S07-34800	0.15	0.004
63	S07-34801	0.09	0.003
64	S07-34802	0.21	0.006
65	S07-34803	0.17	0.005
66	S07-34804	0.18	0.005
67	S07-34805	0.16	0.005
68	S07-34806	0.18	0.005
69	S07-34807	0.17	0.005
70	S07-34808	0.13	0.004
71	S07-34809	0.07	0.002

* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
72	S07-34810	0.18	0.005
73	S07-34811	0.13	0.004
74	S07-34812	2.06	0.060
75	S07-34813	0.22	0.006
76	S07-34814	0.19	0.006
77	S07-34815	0.18	0.005
78	S07-34816	0.17	0.005
79	S07-34817	0.04	0.001
80	S07-34818	0.11	0.003
81	S07-34819	0.15	0.004
82	S07-34820	0.20	0.006
83	S07-34821	0.19	0.006
84	S07-34822	<0.03	<0.001
85	S07-34823	0.14	0.004
86	S07-34824	0.14	0.004
87	S07-34825	0.15	0.004
88	S07-34826	0.16	0.005
89	S07-34827	0.14	0.004
90	S07-34828	0.12	0.004
91	S07-34829	0.14	0.004
92	S07-34830	0.15	0.004
93	S07-34831	0.09	0.003
94	S07-34832	0.08	0.002
95	S07-34833	0.83	0.024
96	S07-34834	0.80	0.023
97	S07-34835	0.29	0.008
98	S07-34836	0.04	0.001
99	S07-34837	0.01	0.000
100	S07-34838	0.06	0.002
101	S07-34839	0.15	0.004
102	S07-34840	0.13	0.004
103	S07-34841	0.38	0.011
104	S07-34842	0.15	0.004
105	S07-34843	0.03	0.001
106	S07-34844	0.05	0.001
107	S07-34845	<0.03	<0.001
108	S07-34846	<0.03	<0.001
109	S07-34847	<0.03	<0.001
110	S07-34848	0.08	0.002
111	S07-34849	0.08	0.002
112	S07-34850	0.08	0.002
113	S07-34851	0.25	0.007
114	S07-34852	0.05	0.002


* = 30g FA

Alan Bruce Jones
 ECO TECH LABORATORY LTD.
 Julia Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
115	S07-34853	0.31	0.009
116	S07-34854	0.58	0.017
117	S07-34855	<0.03	<0.001
118	S07-34856	<0.03	<0.001
119	S07-34857	0.02	0.001
120	S07-34858	0.04	0.001
121	S07-34859	0.11	0.003
122	S07-34860	0.24	0.007
123	S07-34861	* <0.03	<0.001
124	S07-34862	0.07	0.002
125	S07-34863	0.13	0.004
126	S07-34864	0.14	0.004
127	S07-34865	<0.03	<0.001
128	S07-34866	<0.03	<0.001
129	S07-34867	<0.03	<0.001
130	S07-34868	0.04	0.001
131	S07-34869	0.06	0.002
132	S07-34870	* 6.69	0.195
133	S07-34871	0.05	0.001
134	S07-34872	<0.03	<0.001
135	S07-34873	<0.03	<0.001
136	S07-34874	0.19	0.006
137	S07-34875	0.25	0.007
138	S07-34876	1.02	0.030
139	S07-34877	0.12	0.003
140	S07-34878	0.22	0.006
141	S07-34879	0.05	0.002
142	S07-34880	<0.03	<0.001
143	S07-34881	<0.03	<0.001
144	S07-34882	<0.03	<0.001
145	S07-34883	<0.03	<0.001
146	S07-34884	0.05	0.001
147	S07-34885	<0.03	<0.001
148	S07-34886	<0.03	<0.001
149	S07-34887	<0.03	<0.001
150	S07-34888	0.05	0.002
151	S07-34889	<0.03	<0.001
152	S07-34890	* 0.43	0.013
153	S07-34891	0.04	0.001
154	S07-34892	<0.03	<0.001
155	S07-34893	<0.03	<0.001
156	S07-34894	0.03	0.001
157	S07-34895	0.04	0.001


* = 30g FA


ECOTECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
158	S07-34896	<0.03	<0.001
159	S07-34897	<0.03	<0.001
160	S07-34898	0.07	0.002
161	S07-34899	0.32	0.009
162	S07-34900	0.32	0.009
163	S07-34901	0.15	0.004
164	S07-34902	*	<0.03
165	S07-34903	0.06	0.002
166	S07-34904	<0.03	<0.001
167	S07-34905	<0.03	<0.001
168	S07-34906	<0.03	<0.001
169	S07-34907	<0.03	<0.001
170	S07-34908	<0.03	<0.001
171	S07-34909	<0.03	<0.001
172	S07-34910	<0.03	<0.001
173	S07-34911	<0.03	<0.001
174	S07-34912	<0.03	<0.001
175	S07-34913	<0.03	<0.001
176	S07-34914	0.03	0.001
177	S07-34915	0.19	0.006
178	S07-34916	0.43	0.012
179	S07-34917	0.62	0.018
180	S07-34918	<0.03	<0.001
181	S07-34919	<0.03	<0.001
182	S07-34920	<0.03	<0.001
183	S07-34921	<0.03	<0.001
184	S07-34922	<0.03	<0.001
185	S07-34923	<0.03	<0.001
186	S07-34924	<0.03	<0.001
187	S07-34925	0.07	0.002
188	S07-34926	<0.03	<0.001
189	S07-34927	<0.03	<0.001
190	S07-34928	*	<0.03
191	S07-34929	<0.03	<0.001
192	S07-34930	<0.03	<0.001
193	S07-34931	<0.03	<0.001
194	S07-34932	<0.03	<0.001
195	S07-34933	<0.03	<0.001
196	S07-34934	<0.03	<0.001
197	S07-34935	<0.03	<0.001
198	S07-34936	<0.03	<0.001
199	S07-34937	*	2.01
200	S07-34938	<0.03	<0.001
201	S07-34939	<0.03	<0.001

* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer


Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
QC DATA:			
Resplit:			
1	S07-34739	<0.03	<0.001
36	S07-34774	<0.03	<0.001
71	S07-34809	0.07	0.002
106	S07-34844	0.03	0.001
141	S07-34879	<0.03	<0.001
176	S07-34914	0.03	0.001
Standard:			
Ox154		1.90	0.055
Ox154		1.90	0.055
Ox154		1.86	0.054
Ox154		1.90	0.055
Ox154		1.84	0.054
Ox154		1.90	0.055
Ox154		1.88	0.055
Ox154		1.90	0.055
Ox154		1.86	0.054
Ox154		1.91	0.056
Ox154		1.90	0.055
Ox154		1.90	0.055
Ox154		1.90	0.055
Ox154		1.89	0.055
Ox154		1.86	0.054
Ox154		1.84	0.054
Ox154		1.85	0.054
Ox154		1.83	0.053

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw
XLS/07


ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

ECH LABORATORY LTD.

Dallas Drive

NANAIMO, B.C.

4

250-573-5700

250-573-4557

ICP CERTIFICATE OF ANALYSIS A-2007-2297

Skygold Ventures

615 - 800 W. Pender Street

Vancouver, BC

V6B 2V6

No. of samples received: 201

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-160

Samples submitted by: Tasha Gainer

in ppm unless otherwise reported

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
S07-34739	<0.2	4.15	245	265	<5	4.48	<1	35	819	2	3.84	1.63	<10	5.44	1630	<1	0.36	440	540	16	10	<20	340	0.03	<10	70	<10	6	110
S07-34740	<0.2	3.98	115	265	<5	5.48	<1	32	496	2	2.93	1.63	<10	5.91	1698	<1	0.33	342	430	16	5	<20	424	0.03	<10	65	<10	8	86
S07-34741	<0.2	3.63	220	115	<5	7.02	<1	45	726	2	4.36	0.94	<10	7.40	2125	<1	0.36	480	600	16	10	<20	436	0.02	<10	102	<10	7	74
S07-34742	0.2	4.92	210	75	<5	5.42	<1	42	679	3	4.89	0.63	<10	5.58	1528	<1	0.86	334	790	26	5	<20	356	0.05	<10	134	<10	6	81
S07-34743	0.4	3.67	295	105	<5	6.10	<1	43	790	26	4.18	1.00	<10	5.15	1574	<1	0.45	451	470	16	10	<20	417	0.03	<10	94	<10	5	96
S07-34744	0.2	3.41	145	55	<5	5.61	<1	51	807	3	3.97	0.73	<10	6.46	1393	<1	0.47	578	380	18	10	<20	340	0.02	<10	84	<10	5	103
S07-34745	0.4	3.31	145	55	<5	5.56	<1	56	864	3	3.80	0.73	<10	6.63	1361	<1	0.45	601	380	12	10	<20	345	0.02	<10	83	<10	5	107
S07-34746	<0.2	5.05	110	380	<5	4.25	<1	27	468	2	5.01	1.22	<10	5.98	1595	<1	0.95	213	720	20	5	<20	330	0.05	<10	130	<10	5	64
S07-34747	0.8	4.77	95	485	<5	4.34	<1	27	409	94	3.66	1.45	<10	3.90	1425	<1	0.71	138	750	26	<5	<20	321	0.06	<10	120	<10	6	66
S07-34748	0.2	5.63	65	1340	<5	2.14	<1	12	278	3	2.36	1.99	10	2.11	1053	<1	0.40	99	370	22	<5	<20	135	0.09	<10	47	<10	9	46
S07-34749	0.2	5.59	50	1405	<5	1.64	<1	15	240	90	2.28	1.64	10	2.27	1063	<1	0.56	74	460	22	<5	<20	131	0.09	<10	59	<10	8	49
S07-34750	0.2	4.51	50	1040	<5	1.98	<1	15	222	16	2.39	1.62	20	2.57	1381	<1	0.43	94	400	26	<5	<20	167	0.08	<10	55	<10	8	34
S07-34751	1.2	5.10	25	1040	<5	1.91	<1	12	271	35	2.34	1.45	10	2.79	1575	<1	0.77	90	540	20	<5	<20	165	0.09	<10	53	<10	7	50
S07-34752	0.2	3.10	145	450	<5	3.80	<1	30	696	6	3.14	0.87	<10	3.88	2571	1	0.44	261	400	20	10	<20	226	0.03	<10	82	<10	3	87
S07-34753	0.6	4.33	15	1250	<5	0.86	<1	19	207	132	2.50	1.48	20	1.23	1540	<1	0.51	50	440	34	10	<20	88	0.10	<10	103	<10	5	57
S07-34754	<0.2	7.15	<5	500	<5	2.79	<1	10	85	36	3.62	1.10	10	1.35	796	3	2.89	28	830	30	<5	<20	377	0.36	<10	108	<10	18	48
S07-34755	0.6	5.15	25	1340	<5	1.55	<1	24	180	118	3.60	1.72	20	2.09	2690	<1	0.67	54	600	32	<5	<20	139	0.11	<10	133	<10	7	106
S07-34756	0.6	6.21	10	1625	<5	1.86	<1	18	173	59	3.04	1.96	20	2.05	2810	<1	0.76	44	530	42	<5	<20	153	0.14	<10	78	<10	10	84
S07-34757	1.6	5.38	10	1115	<5	1.10	<1	18	225	206	3.27	1.78	20	1.79	2500	<1	0.56	46	610	38	15	<20	107	0.12	<10	87	<10	7	94
S07-34758	0.6	5.67	<5	1280	<5	1.56	<1	13	179	154	2.88	1.93	20	2.02	2926	<1	1.08	30	480	34	<5	<20	151	0.12	<10	71	<10	6	75
S07-34759	0.2	5.19	<5	1190	<5	1.01	<1	11	174	43	2.56	1.70	10	1.76	2417	<1	1.15	22	450	26	<5	<20	108	0.12	<10	62	<10	6	77
S07-34760	0.8	6.06	<5	1025	<5	1.23	<1	10	93	53	3.04	1.61	30	1.80	2812	<1	2.04	17	3500	28	5	<20	150	0.15	<10	87	<10	13	79
S07-34761	0.8	6.71	<5	1340	<5	0.98	<1	9	99	60	2.69	2.09	20	1.73	2566	<1	1.60	14	680	30	<5	<20	111	0.16	<10	72	<10	5	73
S07-34762	0.4	5.53	<5	1290	<5	0.90	<1	4	99	10	1.86	1.70	<10	1.07	1892	<1	1.75	9	410	22	<5	<20	117	0.11	<10	25	<10	4	46
S07-34763	<0.2	5.59	<5	1360	<5	0.93	<1	5	275	5	2.35	2.06	<10	1.32	1995	<1	0.80	12	510	24	<5	<20	103	0.13	<10	40	<10	5	48

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
S07-34764	6.3	3.90	145	350	<5	0.37	<1	7	41	52	3.59	2.91	<10	0.25	228	6	0.48	22	420	28	65	<20	102	0.28	<10	48	<10	10	57
S07-34765	0.4	5.59	<5	1270	<5	0.92	<1	11	163	74	2.86	1.93	20	1.75	2571	<1	0.89	21	580	32	<5	<20	97	0.15	<10	70	<10	7	73
S07-34766	1.0	4.98	5	1150	<5	1.50	<1	13	179	55	2.41	1.86	10	1.75	2161	<1	0.60	30	510	22	<5	<20	128	0.13	<10	61	<10	6	58
S07-34767	1.8	3.75	75	730	<5	3.34	<1	38	590	21	3.68	1.37	10	5.03	2002	<1	0.22	305	380	24	10	<20	272	0.09	<10	108	<10	6	79
S07-34768	0.6	5.67	60	835	<5	1.24	<1	23	146	77	3.54	1.70	20	2.50	1522	4	0.19	86	640	38	<5	<20	116	0.16	<10	103	<10	10	89
S07-34769	0.6	5.51	45	275	<5	1.44	1	23	109	107	4.56	1.53	20	2.34	1740	14	0.19	90	780	46	<5	<20	108	0.14	<10	183	<10	10	132
S07-34770	0.8	5.74	35	1010	<5	1.32	<1	28	98	158	4.20	1.52	20	2.49	2346	<1	0.36	73	630	36	<5	<20	119	0.16	<10	121	<10	9	82
S07-34771	0.2	5.38	20	1195	<5	1.02	<1	11	98	51	2.41	1.91	20	1.83	1575	<1	0.23	43	370	28	<5	<20	93	0.15	<10	49	<10	10	56
S07-34772	0.4	3.60	20	630	<5	1.36	<1	13	229	68	2.34	1.42	10	1.96	1132	2	0.22	53	320	26	<5	<20	127	0.09	<10	33	<10	6	52
S07-34773	1.2	4.50	65	595	<5	5.75	<1	35	522	3	4.49	1.74	<10	6.09	2533	<1	0.38	264	600	26	<5	<20	494	0.05	<10	104	<10	7	83
S07-34774	0.6	3.61	55	355	<5	2.65	<1	21	254	111	2.64	1.01	10	2.51	1304	<1	0.66	105	520	36	<5	<20	212	0.07	<10	56	<10	6	46
S07-34775	0.4	5.99	25	800	<5	2.57	<1	18	244	97	3.08	1.84	10	3.17	1555	<1	1.07	80	740	30	<5	<20	260	0.10	<10	94	<10	7	53
S07-34776	0.6	7.20	<5	1685	<5	1.15	<1	6	223	19	2.39	2.37	20	2.00	1759	<1	0.38	17	470	32	<5	<20	109	0.18	<10	32	<10	9	50
S07-34777	1.6	5.69	<5	1070	<5	0.56	<1	6	121	73	2.19	2.13	10	1.50	707	<1	0.54	17	320	22	<5	<20	70	0.14	<10	30	<10	6	43
S07-34778	<0.2	4.41	45	285	<5	4.95	<1	36	452	18	4.69	1.12	<10	6.09	1445	<1	0.74	195	620	18	5	<20	338	0.05	<10	134	<10	6	61
S07-34779	<0.2	0.08	<5	10	<5	>10	<1	<1	3	<1	0.15	<0.01	<10	1.38	52	<1	0.01	13	50	<2	<5	<20	5383	<0.01	<10	2	<10	<1	5
S07-34780	0.8	4.96	50	425	<5	2.75	<1	33	581	28	2.90	1.66	10	4.17	1202	<1	0.68	319	550	20	5	<20	179	0.07	<10	74	<10	6	67
S07-34781	0.2	3.82	65	255	<5	5.84	<1	42	669	7	4.07	1.25	<10	6.87	2065	<1	0.55	421	570	18	10	<20	296	0.04	<10	89	<10	7	86
S07-34782	2.2	6.60	25	455	<5	3.42	<1	25	296	56	4.51	1.55	<10	4.07	1410	<1	1.17	102	920	38	<5	<20	260	0.09	<10	130	<10	7	63
S07-34783	0.6	4.85	35	200	<5	5.08	<1	34	504	13	4.93	1.02	<10	7.08	1538	<1	0.90	264	780	18	5	<20	315	0.06	<10	140	<10	5	55
S07-34784	0.6	5.08	30	530	<5	3.04	<1	17	322	24	2.46	1.50	10	3.95	1142	<1	0.61	133	340	22	<5	<20	192	0.07	<10	45	<10	8	41
S07-34785	1.4	5.41	20	710	<5	1.94	<1	17	212	21	2.56	1.69	10	3.19	1220	<1	0.42	89	400	24	<5	<20	126	0.10	<10	56	<10	8	53
S07-34786	<0.2	5.02	40	330	<5	2.89	<1	31	530	20	4.75	1.31	10	5.70	2131	<1	0.78	229	650	26	<5	<20	189	0.06	<10	104	<10	5	88
S07-34787	0.2	4.48	25	225	<5	4.13	<1	31	497	70	4.65	1.25	<10	4.97	1755	<1	0.66	183	670	22	5	<20	231	0.08	<10	130	<10	5	67
S07-34788	0.8	5.70	90	305	<5	0.21	<1	8	25	32	3.24	4.33	10	0.29	163	3	0.06	15	480	22	35	<20	49	0.35	<10	62	<10	10	49
S07-34789	1.6	4.20	40	210	<5	5.54	<1	39	610	77	4.56	1.15	<10	6.63	2079	<1	0.64	278	820	18	20	<20	242	0.06	<10	147	<10	6	63
S07-34790	1.2	6.14	15	130	<5	2.13	<1	18	130	161	3.68	2.51	20	1.64	1344	<1	0.38	48	600	42	<5	<20	131	0.14	<10	112	<10	6	41
S07-34791	0.2	4.81	25	475	<5	2.27	<1	18	204	35	2.88	1.55	20	2.89	1524	5	0.45	79	600	26	<5	<20	149	0.10	<10	83	<10	7	63
S07-34792	0.6	6.28	10	900	<5	2.01	<1	12	126	77	2.34	2.59	20	1.59	1014	5	0.26	40	500	34	<5	<20	111	0.12	<10	80	<10	9	37
S07-34793	0.6	6.63	15	370	<5	4.00	<1	23	239	84	3.76	2.39	10	2.59	2133	<1	0.47	65	830	44	<5	<20	178	0.11	<10	134	<10	8	58
S07-34794	0.4	6.07	15	340	<5	3.74	<1	20	203	69	3.31	2.27	10	2.35	2001	<1	0.44	52	780	40	<5	<20	168	0.11	<10	124	<10	8	48
S07-34795	0.4	4.39	25	415	<5	3.16	<1	31	593	57	3.73	1.57	10	3.04	1171	9	0.25	194	500	36	5	<20	169	0.07	<10	115	<10	7	129
S07-34796	1.0	6.68	10	90	<5	1.57	3	13	155	132	2.90	2.85	20	1.19	802	24	0.30	55	640	32	<5	<20	84	0.11	<10	175	<10	6	176
S07-34797	1.0	6.47	40	305	<5	2.47	<1	20	278	147	4.90	2.69	10	1.59	1056	22	0.23	88	630	52	<5	<20	123	0.09	<10	177	<10	7	91
S07-34798	1.4	4.67	20	110	<5	2.79	4	15	279	72	3.85	1.95	20	1.56	840	26	0.13	71	900	40	10	<20	116	0.07	<10	234	<10	7	240
S07-34799	1.4	4.89	10	110	<5	3.01	3	13	245	52	4.07	1.98	20	1.71	830	28	0.12	69	770	52	10	<20	117	0.07	<10	204	<10	7	207
S07-34800	2.2	5.32	15	150	<5	2.00	2	15	253	54	4.36	2.20	20	1.70	664	26	0.16	72	720	42	5	<20	86	0.07	<10	193	<10	7	172
S07-34801	0.6	3.76	95	295	<5	5.11	2	37	1069	93	4.63	1.45	10	4.45	1510	22	0.17	509	500	108	10	<20	214	0.04	<10	130	<10	6	197
S07-34802	2.4	4.10	30	105	<5	3.00	3	20	406	101	4.94	1.72	20	2.22	863	30	0.12	147	710	54	15	<20	119	0.06	<10	204	<10	6	186
S07-34803	2.2	4.16	25	165	<5	2.85	3	17	201	64	3.89	1.56	20	1.69	762	24	0.09	91	950	104	10	<20	144	0.08	<10	178	<10	9	186

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
S07-34804	2.8	5.04	20	150	<5	2.82	3	14	248	61	5.00	1.94	20	1.55	745	36	0.11	79	770	64	10	<20	114	0.10	<10	211	<10	9	224
S07-34805	3.4	4.99	20	140	<5	2.71	4	14	236	75	4.84	2.00	20	1.43	715	36	0.11	79	830	94	10	<20	104	0.10	<10	227	<10	8	241
S07-34806	2.8	4.90	10	205	<5	2.50	3	12	235	78	4.31	2.15	20	1.41	689	32	0.13	68	740	68	10	<20	99	0.08	<10	214	<10	7	204
S07-34807	3.2	5.01	15	135	<5	2.63	3	13	231	56	4.51	2.11	20	1.38	719	35	0.12	72	810	66	10	<20	101	0.09	<10	215	<10	8	224
S07-34808	2.4	4.26	10	175	<5	3.75	3	10	241	54	3.32	1.61	20	1.86	1099	23	0.11	55	760	56	10	<20	155	0.08	<10	171	<10	7	195
S07-34809	1.2	3.58	10	140	<5	3.13	3	12	205	65	3.27	1.46	20	1.39	1010	26	0.09	64	750	36	5	<20	131	0.08	<10	150	<10	6	217
S07-34810	2.6	4.44	10	110	<5	2.39	2	12	205	64	4.17	1.82	20	1.21	709	30	0.11	68	680	56	10	<20	95	0.09	<10	177	<10	7	140
S07-34811	1.6	4.98	15	200	<5	3.97	1	16	396	47	4.19	1.89	20	1.97	1048	20	0.22	74	690	46	10	<20	175	0.11	<10	161	<10	8	114
S07-34812	4.6	4.50	115	245	<5	0.45	1	11	37	592	4.97	2.42	10	1.73	382	7	0.27	25	530	106	45	<20	72	0.28	<10	54	<10	11	686
S07-34813	3.6	4.93	15	195	<5	2.06	2	12	220	59	4.22	2.07	20	1.15	622	31	0.13	65	770	64	10	<20	87	0.10	<10	181	<10	9	170
S07-34814	3.2	4.91	15	120	<5	3.01	2	11	242	57	4.06	1.74	20	1.58	959	28	0.11	63	750	66	10	<20	112	0.10	<10	179	<10	8	167
S07-34815	2.6	4.19	10	120	<5	2.68	2	11	469	53	3.72	1.63	20	1.41	810	28	0.09	60	670	52	10	<20	109	0.09	<10	168	<10	7	180
S07-34816	2.0	4.31	10	155	<5	1.78	2	14	239	59	4.85	1.86	20	1.04	576	33	0.12	77	670	56	5	<20	89	0.11	<10	210	<10	7	178
S07-34817	0.8	5.25	40	355	<5	5.34	<1	23	456	57	3.81	2.09	10	3.76	1558	10	0.45	162	550	30	10	<20	281	0.09	<10	144	<10	9	106
S07-34818	1.6	4.33	25	170	<5	5.76	2	21	373	87	4.51	1.57	10	2.70	1614	21	0.34	163	720	44	10	<20	256	0.07	<10	153	<10	7	139
S07-34819	2.0	4.49	15	210	<5	2.67	3	15	234	65	3.98	1.81	20	1.41	717	29	0.25	77	620	52	5	<20	125	0.10	<10	198	<10	7	208
S07-34820	3.0	4.81	20	120	<5	3.33	3	17	275	79	4.64	1.79	20	1.70	919	29	0.23	85	890	60	10	<20	162	0.11	<10	201	<10	9	201
S07-34821	3.2	4.99	15	145	<5	2.72	3	15	311	70	4.63	1.99	20	1.39	714	31	0.20	75	1260	68	10	<20	131	0.12	<10	212	<10	8	215
S07-34822	<0.2	0.10	<5	40	<5	>10	<1	<1	6	2	0.60	0.04	<10	>10	208	<1	0.01	3	170	<2	<5	<20	49	<0.01	<10	5	<10	<1	15
S07-34823	2.2	4.49	15	150	<5	3.44	3	17	222	73	4.56	1.69	20	1.68	1011	28	0.13	98	910	54	10	<20	157	0.11	<10	225	<10	7	210
S07-34824	2.2	5.51	15	130	<5	3.14	3	16	237	63	4.35	2.10	20	1.52	967	20	0.38	66	1190	64	10	<20	143	0.14	<10	232	<10	8	204
S07-34825	2.0	4.67	15	225	<5	2.52	4	16	415	105	4.61	1.83	20	1.23	778	31	0.29	81	1100	58	10	<20	124	0.11	<10	254	<10	7	273
S07-34826	2.2	4.66	15	100	<5	2.46	4	16	628	85	4.56	1.78	20	1.23	863	34	0.27	87	920	58	15	<20	122	0.12	<10	255	<10	7	278
S07-34827	2.4	4.70	10	180	<5	2.43	4	17	240	72	4.33	1.86	20	1.16	802	26	0.19	74	1120	66	10	<20	118	0.12	<10	257	<10	7	261
S07-34828	2.2	5.29	10	185	<5	2.64	3	18	284	56	4.19	1.95	20	1.29	929	24	0.30	69	990	54	10	<20	128	0.14	<10	232	<10	8	236
S07-34829	2.6	4.73	15	165	<5	2.52	3	17	356	60	4.34	1.85	20	1.16	850	28	0.23	75	1080	58	10	<20	123	0.12	<10	244	<10	7	260
S07-34830	2.6	4.86	15	230	<5	2.59	3	17	337	58	4.53	1.84	20	1.20	895	30	0.22	78	1140	64	15	<20	126	0.12	<10	246	<10	7	250
S07-34831	2.4	4.92	15	325	<5	2.28	3	16	222	51	4.03	1.90	20	1.06	723	26	0.22	71	1100	50	10	<20	115	0.12	<10	251	<10	7	212
S07-34832	1.4	4.61	10	245	<5	2.40	2	17	295	59	4.26	1.79	20	1.08	771	23	0.18	71	1110	36	5	<20	127	0.13	<10	242	<10	7	160
S07-34833	1.2	5.10	10	140	<5	2.96	2	12	232	114	3.77	1.81	20	1.40	1010	17	0.55	49	1260	28	<5	<20	179	0.14	<10	225	<10	7	171
S07-34834	1.4	6.33	15	190	<5	3.39	<1	14	339	225	3.71	1.92	20	1.54	1297	13	1.00	44	920	26	<5	<20	206	0.17	<10	224	<10	8	90
S07-34835	0.4	6.37	10	190	<5	2.70	<1	11	123	82	2.72	1.74	20	1.46	761	23	1.50	31	700	28	<5	<20	212	0.14	<10	171	<10	7	73
S07-34836	0.6	6.30	<5	625	<5	2.93	<1	10	234	63	2.49	1.42	20	1.38	925	4	2.26	23	580	28	<5	<20	255	0.15	<10	120	<10	7	55
S07-34837	0.4	6.62	10	480	<5	2.28	<1	11	197	70	2.53	1.74	20	1.39	707	10	1.75	24	620	28	<5	<20	211	0.14	<10	137	<10	7	69
S07-34838	0.4	7.04	10	290	<5	3.16	1	18	315	110	3.89	1.86	20	1.64	833	12	1.72	44	740	32	<5	<20	237	0.17	<10	204	<10	7	122
S07-34839	1.4	5.81	5	270	<5	2.79	<1	15	159	103	3.42	1.47	20	1.36	653	<1	1.68	36	850	26	<5	<20	232	0.18	<10	111	<10	8	70
S07-34840	0.6	6.42	10	140	<5	4.25	<1	19	145	134	4.95	1.62	20	1.87	902	3	1.68	37	920	36	<5	<20	261	0.17	<10	162	<10	7	88
S07-34841	0.4	5.93	10	200	<5	3.79	2	17	196	93	3.84	1.55	10	1.57	755	43	1.04	58	930	28	<5	<20	243	0.18	<10	475	<10	7	147
S07-34842	0.4	6.82	10	195	<5	4.23	<1	17	108	93	4.35	1.61	20	1.71	827	15	1.53	40	1010	38	<5	<20	260	0.18	<10	285	<10	7	103
S07-34843	0.8	8.37	<5	415	<5	4.56	1	18	147	108	4.97	2.01	10	2.07	977	5	1.90	27	1030	58	<5	<20	327	0.21	<10	253	<10	8	153

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn	
S07-34844	0.4	6.66	10	340	<5	5.77	1	15	118	62	4.54	2.00	20	2.10	1179	10	1.34	29	1950	38	<5	<20	322	0.12	<10	204	<10	10	135
S07-34845	0.6	6.08	5	335	<5	3.70	1	16	196	84	3.80	1.91	20	1.49	656	12	1.13	40	960	32	<5	<20	229	0.12	<10	253	<10	7	136
S07-34846	0.4	5.47	5	400	<5	3.83	1	13	277	69	3.52	1.40	20	1.44	730	10	1.55	33	820	32	<5	<20	224	0.11	<10	190	<10	7	122
S07-34847	0.2	5.61	<5	420	<5	3.81	1	13	164	64	3.35	1.46	20	1.49	763	10	1.66	31	890	30	<5	<20	232	0.12	<10	204	<10	7	119
S07-34848	0.8	6.01	10	225	<5	3.77	1	14	334	77	4.13	1.70	20	1.45	734	18	1.37	35	1070	38	<5	<20	236	0.11	<10	167	<10	8	138
S07-34849	1.0	7.18	5	450	<5	3.91	1	13	98	130	3.86	2.17	20	1.62	677	11	1.82	31	980	50	<5	<20	255	0.16	<10	216	<10	12	193
S07-34850	0.6	6.75	20	190	<5	3.71	1	16	284	92	4.48	1.99	20	1.51	709	10	1.62	38	800	38	<5	<20	221	0.13	<10	226	<10	8	134
S07-34851	0.2	5.59	15	245	<5	3.99	3	18	348	77	4.32	1.59	20	1.47	858	11	1.19	41	950	30	<5	<20	205	0.11	<10	211	<10	7	267
S07-34852	0.4	6.75	10	330	<5	5.24	2	17	154	115	4.42	1.99	20	2.02	961	13	1.29	34	850	32	<5	<20	276	0.13	<10	278	<10	9	210
S07-34853	0.4	6.64	10	350	<5	3.67	1	13	149	84	3.41	2.24	20	1.58	771	14	1.10	38	770	28	<5	<20	228	0.12	<10	238	<10	9	124
S07-34854	0.6	5.56	15	160	<5	3.29	1	17	101	65	4.07	1.68	20	1.35	1040	11	0.38	43	740	32	<5	<20	222	0.08	<10	172	<10	8	121
S07-34855	0.4	5.55	10	365	<5	3.27	1	15	101	83	3.19	1.63	20	1.58	990	7	0.90	28	850	30	<5	<20	214	0.09	<10	159	<10	8	139
S07-34856	0.4	4.59	5	420	<5	3.36	<1	8	140	55	2.54	1.35	10	1.24	794	8	0.87	25	610	24	<5	<20	201	0.09	<10	137	<10	7	101
S07-34857	0.6	6.87	15	335	<5	3.75	2	15	88	86	4.21	1.84	20	1.59	827	27	1.92	50	810	36	<5	<20	239	0.10	<10	234	<10	8	167
S07-34858	0.6	6.77	15	280	<5	2.88	2	18	83	99	3.82	2.02	20	1.45	650	15	1.02	40	940	32	<5	<20	234	0.13	<10	235	<10	9	163
S07-34859	0.8	6.02	15	285	<5	2.87	1	16	141	76	3.77	1.84	20	1.54	859	9	0.47	35	730	30	<5	<20	250	0.12	<10	178	<10	9	144
S07-34860	0.6	6.44	10	325	<5	3.92	2	15	90	129	3.86	2.21	20	1.73	1022	14	0.75	37	950	32	<5	<20	259	0.13	<10	259	<10	9	153
S07-34861	<0.2	0.14	<5	95	<5	>10	<1	<1	<1	1	0.56	0.03	<10	>10	192	<1	0.05	3	160	<2	<5	<20	51	<0.01	<10	1	<10	<1	15
S07-34862	0.2	4.49	10	280	<5	3.74	<1	12	142	71	2.67	1.45	20	1.30	1170	9	0.47	34	870	24	<5	<20	257	0.10	<10	151	<10	8	90
S07-34863	0.6	6.38	15	260	<5	4.03	1	16	126	90	3.76	1.95	20	1.71	964	15	0.43	35	750	32	<5	<20	341	0.14	<10	237	<10	10	149
S07-34864	0.6	6.39	20	260	<5	4.74	2	18	101	93	4.38	1.81	20	1.87	1286	14	0.44	41	780	34	<5	<20	359	0.13	<10	234	<10	10	160
S07-34865	0.4	4.65	10	425	<5	4.64	<1	18	150	77	3.20	1.45	10	1.37	1845	6	0.40	50	740	24	<5	<20	276	0.09	<10	117	<10	7	90
S07-34866	0.6	5.52	10	590	<5	3.03	1	17	201	67	3.13	2.10	10	1.08	1159	14	0.46	52	1390	28	<5	<20	154	0.11	<10	154	<10	7	134
S07-34867	0.6	6.28	10	235	<5	2.64	1	17	164	76	3.06	2.24	20	1.30	810	10	1.12	48	2380	32	<5	<20	165	0.11	<10	177	<10	9	128
S07-34868	0.4	6.87	10	740	<5	2.90	<1	22	187	62	4.50	2.04	10	1.63	962	7	1.65	33	880	40	<5	<20	197	0.12	<10	157	<10	7	117
S07-34869	0.4	5.91	10	390	<5	2.48	<1	19	125	63	4.44	1.83	10	1.40	596	24	1.10	40	650	36	<5	<20	174	0.09	<10	199	<10	7	130
S07-34870	6.2	3.89	125	330	<5	0.37	<1	7	38	50	3.74	3.08	<10	0.27	228	6	0.48	21	410	20	60	<20	101	0.28	<10	49	<10	10	47
S07-34871	0.6	6.38	15	200	<5	3.52	3	17	178	99	3.85	2.13	20	1.54	674	29	1.04	49	830	28	<5	<20	204	0.11	<10	348	<10	5	219
S07-34872	0.6	6.46	10	290	<5	4.01	2	15	152	83	3.97	1.94	20	1.74	739	14	1.56	32	1230	28	<5	<20	229	0.13	<10	218	<10	9	189
S07-34873	0.6	6.95	15	230	<5	3.16	1	18	191	83	4.60	1.84	20	1.60	605	11	2.01	33	770	30	<5	<20	226	0.14	<10	237	<10	7	158
S07-34874	0.6	5.97	20	415	<5	4.16	2	17	177	71	4.11	1.63	10	1.49	782	23	1.39	41	980	32	<5	<20	282	0.11	<10	215	<10	7	169
S07-34875	0.4	5.77	20	340	<5	2.94	<1	22	140	91	3.62	2.17	20	1.40	1527	8	0.29	53	730	30	<5	<20	192	0.11	<10	155	<10	8	74
S07-34876	1.6	4.84	10	275	<5	2.53	<1	25	112	131	3.27	2.07	20	1.17	2440	7	0.29	57	460	34	<5	<20	120	0.10	<10	92	<10	7	88
S07-34877	0.8	3.78	15	325	<5	2.54	<1	25	117	163	2.87	1.55	20	1.16	2564	7	0.22	58	360	36	<5	<20	115	0.07	<10	75	<10	6	103
S07-34878	1.4	3.29	15	205	<5	2.50	<1	32	167	153	3.17	1.37	20	1.16	2497	9	0.22	58	320	40	<5	<20	109	0.06	<10	77	<10	5	102
S07-34879	0.6	4.14	25	655	<5	2.26	<1	21	137	135	2.42	1.66	20	1.18	1819	8	0.44	56	400	32	<5	<20	103	0.09	<10	87	<10	6	94
S07-34880	0.4	5.26	10	1545	<5	1.73	<1	12	143	73	2.32	1.90	10	1.27	971	5	0.84	28	500	32	<5	<20	96	0.10	<10	130	<10	6	122
S07-34881	0.4	5.24	5	1625	<5	1.81	<1	7	136	36	2.27	1.95	10	1.36	759	3	0.94	17	420	28	<5	<20	101	0.10	<10	109	<10	6	82
S07-34882	0.2	5.40	10	1165	<5	2.04	<1	8	118	39	2.22	1.83	20	1.28	748	6	1.19	18	490	34	<5	<20	115	0.08	<10	102	<10	6	106
S07-34883	0.2	5.42	5	1570	<5	2.11	<1	7	127	34	2.27	1.89	20	1.39	778	6	1.24	17	500	30	<5	<20	117	0.10	<10	111	<10	6	94

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	W	Y	Zn		
S07-34884	0.8	6.29	10	320	<5	1.68	<1	14	147	41	2.77	2.33	20	1.41	525	4	1.12	26	500	42	<5	<20	100	0.10	<10	123	<10	7	86
S07-34885	<0.2	4.88	15	510	<5	2.00	<1	9	149	31	2.30	1.57	10	1.25	556	3	1.12	21	440	28	<5	<20	110	0.08	<10	111	<10	6	81
S07-34886	0.2	5.96	5	1850	<5	2.03	<1	5	109	35	2.27	2.17	20	1.54	569	8	1.25	16	500	32	<5	<20	117	0.09	<10	108	<10	7	90
S07-34887	0.4	4.19	10	860	<5	1.25	<1	7	98	30	1.98	1.25	10	0.86	349	8	1.30	22	420	24	<5	<20	84	0.09	<10	127	<10	4	91
S07-34888	0.8	6.90	10	305	<5	1.98	1	18	135	71	3.42	2.15	20	1.29	547	12	1.67	36	700	46	<5	<20	128	0.10	<10	217	<10	6	138
S07-34889	0.4	6.45	10	300	<5	2.22	2	14	154	84	3.54	1.97	20	1.55	615	16	1.73	43	740	38	<5	<20	145	0.11	<10	265	<10	6	199
S07-34890	0.8	5.66	95	330	<5	0.22	<1	7	24	35	3.22	4.50	10	0.29	161	3	0.07	14	470	18	35	<20	40	0.35	<10	65	<10	11	52
S07-34891	0.4	7.36	5	195	<5	2.23	1	19	111	74	3.38	2.41	10	1.55	584	10	1.82	30	930	38	<5	<20	156	0.12	<10	202	<10	6	129
S07-34892	0.4	7.97	<5	1815	<5	2.43	<1	12	69	67	3.96	2.48	10	2.16	778	<1	2.14	18	960	50	<5	<20	190	0.13	<10	137	<10	7	111
S07-34893	0.2	7.54	5	1655	<5	2.04	<1	13	81	44	3.49	2.31	10	1.98	670	<1	2.05	16	740	38	<5	<20	170	0.12	<10	136	<10	6	93
S07-34894	<0.2	7.76	5	1820	<5	2.50	<1	11	104	42	3.12	2.63	10	1.85	730	1	1.67	17	710	30	<5	<20	187	0.11	<10	151	<10	5	70
S07-34895	0.4	6.77	10	880	<5	3.08	<1	20	231	63	3.78	2.14	10	1.26	819	37	1.73	40	1270	32	<5	<20	203	0.12	<10	192	<10	7	71
S07-34896	0.4	7.51	10	325	<5	4.46	<1	14	110	74	3.74	2.15	10	1.84	992	2	2.22	24	1100	34	<5	<20	269	0.12	<10	133	<10	7	66
S07-34897	0.6	8.08	10	1000	<5	3.62	<1	14	74	62	3.21	2.41	10	1.80	831	1	2.51	21	970	38	<5	<20	251	0.13	<10	153	<10	6	79
S07-34898	0.4	7.18	10	505	<5	2.98	<1	19	102	90	3.17	2.25	20	1.66	996	39	1.72	31	970	36	<5	<20	223	0.13	<10	140	<10	7	84
S07-34899	0.8	4.47	10	405	<5	3.85	1	9	189	127	3.35	1.90	20	1.82	1185	23	0.37	41	810	36	<5	<20	224	0.07	<10	137	<10	9	89
S07-34900	0.8	4.75	5	290	<5	2.03	2	11	238	155	3.81	2.33	20	1.57	860	32	0.12	49	840	46	<5	<20	121	0.09	<10	162	<10	10	147
S07-34901	0.2	4.94	10	280	<5	1.83	1	7	131	93	2.86	2.35	20	1.38	642	16	0.14	32	510	32	<5	<20	105	0.08	<10	120	<10	9	107
S07-34902	<0.2	0.08	<5	20	<5	>10	<1	<1	1	<1	0.04	<0.01	<10	1.57	20	<1	0.01	17	40	<2	<5	<20	5754	<0.01	<10	1	<10	<1	4
S07-34903	0.4	5.22	15	430	<5	1.78	2	8	140	64	3.10	2.52	20	1.27	553	19	0.16	34	580	28	<5	<20	110	0.08	<10	128	<10	9	114
S07-34904	0.4	5.08	10	255	<5	2.05	2	9	127	50	3.10	2.41	20	1.32	654	21	0.14	36	610	38	<5	<20	121	0.08	<10	122	<10	9	127
S07-34905	0.6	4.84	20	300	<5	2.90	1	9	172	58	3.13	2.31	20	1.60	864	23	0.11	44	660	28	<5	<20	160	0.08	<10	128	<10	8	95
S07-34906	0.4	4.50	10	220	<5	1.73	<1	9	217	31	2.93	2.18	20	1.29	576	18	0.13	41	490	28	<5	<20	101	0.07	<10	120	<10	8	48
S07-34907	<0.2	4.67	50	1030	<5	3.96	<1	40	809	42	4.06	2.04	10	5.50	1608	2	0.36	324	510	30	10	<20	251	0.05	<10	113	<10	6	143
S07-34908	0.2	3.70	75	265	<5	3.80	<1	40	851	25	3.68	1.55	<10	5.54	1673	<1	0.33	374	450	22	10	<20	279	0.04	<10	105	<10	5	128
S07-34909	<0.2	4.94	35	900	<5	2.34	<1	15	226	54	2.36	2.29	20	2.54	1073	2	0.19	63	370	24	<5	<20	155	0.06	<10	74	<10	7	41
S07-34910	0.4	3.54	25	455	<5	3.80	<1	29	407	49	4.17	1.49	<10	4.37	1875	<1	0.27	190	450	26	<5	<20	240	0.04	<10	74	<10	5	108
S07-34911	0.2	5.08	80	725	<5	3.21	<1	40	641	47	4.81	2.25	10	4.84	1677	2	0.31	302	560	28	5	<20	240	0.07	<10	120	<10	6	104
S07-34912	0.4	4.43	40	485	<5	3.92	<1	28	559	29	3.63	1.77	<10	4.95	1337	4	0.33	220	510	22	10	<20	388	0.06	<10	107	<10	6	74
S07-34913	0.4	4.73	35	330	<5	4.39	<1	24	447	130	4.39	2.06	10	3.72	1418	13	0.21	177	440	32	10	<20	400	0.06	<10	116	<10	7	57
S07-34914	0.5	3.31	55	320	<5	5.71	<1	32	481	58	4.07	1.41	<10	4.10	1934	11	0.14	254	510	28	5	<20	575	0.05	<10	112	<10	7	94
S07-34915	1.0	4.34	40	145	<5	4.21	2	28	333	69	4.12	1.93	10	2.58	1527	19	0.11	209	940	38	5	<20	304	0.08	<10	198	<10	7	196
S07-34916	0.6	4.49	10	280	<5	2.72	3	16	153	61	3.78	2.12	20	1.38	935	23	0.09	70	1190	28	<5	<20	178	0.09	<10	226	<10	7	209
S07-34917	0.6	5.14	10	290	<5	2.64	1	18	151	89	3.94	2.30	20	1.37	926	21	0.12	71	1140	26	<5	<20	191	0.11	<10	288	<10	8	92
S07-34918	0.2	5.77	15	1090	<5	2.36	<1	9	191	27	2.24	2.65	20	2.17	1024	<1	0.19	57	380	28	<5	<20	173	0.09	<10	67	<10	9	44
S07-34919	0.2	5.66	5	1260	<5	0.97	<1	5	111	26	1.63	2.72	20	1.47	759	<1	0.15	12	260	42	<5	<20	74	0.10	<10	52	<10	7	34
S07-34920	<0.2	4.60	<5	1025	<5	1.69	<1	3	84	5	1.14	2.23	20	1.40	1150	<1	0.11	9	190	18	<5	<20	128	0.08	<10	25	<10	9	23
S07-34921	<0.2	5.12	<5	1115	<5	1.98	<1	3	74	6	1.23	2.46	20	1.56	1228	<1	0.15	10	210	18	<5	<20	139	0.08	<10	28	<10	9	29
S07-34922	0.2	5.54	5	1350	<5	1.91	<1	5	83	19	1.92	2.83	30	1.62	1675	<1	0.23	12	330	22	<5	<20	118	0.11	<10	85	<10	7	46
S07-34923	0.2	5.64	5	1320	<5	0.81	<1	5	67	18	1.68	2.62	20	1.20	776	<1	0.23	10	280	22	<5	<20	66	0.10	<10	70	<10	7	40


Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Ca %	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	Y	Zn			
S07-34924	0.4	6.30	5	1445	<5	0.74	<1	4	55	16	1.48	2.85	20	1.17	631	<1	0.32	11	290	20	<5	<20	73	0.11	<10	27	<10	7	32
S07-34925	0.2	5.11	30	570	<5	2.19	<1	24	305	38	2.62	1.34	20	2.89	1574	<1	1.22	132	480	34	<5	<20	208	0.09	<10	61	<10	8	70
S07-34926	0.2	5.99	25	740	<5	2.33	<1	17	308	26	2.83	1.87	10	3.23	1510	<1	0.82	104	540	20	<5	<20	222	0.09	<10	76	<10	6	80
S07-34927	0.2	5.28	20	840	<5	2.91	<1	13	228	11	2.52	1.85	10	2.87	1422	<1	0.57	73	500	18	<5	<20	223	0.09	<10	55	<10	8	40
S07-34928	<0.2	0.04	<5	30	<5	>10	<1	<1	3	2	0.53	0.02	<10	>10	197	<1	0.02	3	180	<2	<5	<20	46	<0.01	<10	2	<10	<1	13
S07-34929	0.2	4.74	15	735	<5	2.43	<1	7	135	7	2.31	1.88	10	2.49	1379	2	0.56	39	420	18	<5	<20	176	0.10	<10	52	<10	6	33
S07-34930	0.4	6.26	5	780	<5	0.99	<1	4	75	63	2.31	1.65	10	1.73	1042	<1	2.38	12	480	20	<5	<20	137	0.14	<10	34	<10	6	40
S07-34931	0.8	6.29	10	840	<5	0.90	<1	7	82	82	2.39	1.76	10	1.48	713	<1	2.47	13	480	56	<5	<20	131	0.15	<10	40	<10	6	43
S07-34932	0.4	5.76	10	690	<5	1.57	<1	5	129	14	2.38	2.02	20	1.64	1375	<1	1.25	21	310	62	<5	<20	152	0.11	<10	44	<10	5	25
S07-34933	0.6	5.91	15	120	<5	0.95	<1	8	103	88	2.55	0.59	10	1.73	816	<1	3.20	23	390	22	<5	<20	183	0.12	<10	27	<10	5	64
S07-34934	0.2	5.15	50	325	<5	4.44	<1	28	442	47	3.79	1.15	<10	5.50	1458	<1	1.40	195	600	22	<5	<20	369	0.07	<10	109	<10	7	49
S07-34935	0.2	3.76	50	140	<5	5.01	<1	29	494	2	3.05	0.83	<10	6.04	1488	<1	0.76	263	390	14	5	<20	338	0.04	<10	72	<10	6	46
S07-34936	<0.2	4.02	45	115	<5	4.52	<1	22	387	27	2.64	0.66	<10	5.16	1302	1	1.49	223	340	20	<5	<20	291	0.04	<10	54	<10	8	37
S07-34937	4.4	4.57	120	260	<5	0.51	<1	12	34	630	4.85	2.66	10	1.75	383	7	0.25	24	510	98	45	<20	73	0.27	<10	54	<10	11	670
S07-34938	0.2	4.33	45	65	<5	6.37	<1	41	675	51	4.68	0.34	<10	8.27	1384	<1	0.78	380	670	18	5	<20	354	0.03	<10	132	<10	6	54
S07-34939	0.4	5.42	30	110	<5	4.49	<1	40	445	108	4.23	0.65	<10	6.14	1168	<1	1.50	207	730	26	<5	<20	334	0.05	<10	140	<10	6	41
A:																													
S07-34739	0.2	4.28	250	280	<5	4.35	<1	34	853	3	4.11	1.70	<10	5.56	1644	<1	0.37	444	550	20	10	<20	344	0.03	<10	70	<10	6	113
S07-34748	0.3	5.76	65	1330	<5	2.24	<1	12	276	3	2.37	1.74	10	2.10	1082	<1	0.40	102	380	20	<5	<20	134	0.09	<10	47	<10	8	44
S07-34757	1.3	5.36	5	1135	<5	1.16	<1	19	220	211	3.54	1.86	20	1.84	2618	<1	0.58	47	640	40	20	<20	109	0.13	<10	87	<10	6	98
S07-34774	0.6	3.68	50	355	<5	2.71	<1	20	259	115	2.76	1.03	10	2.54	1315	<1	0.67	102	520	40	<5	<20	216	0.07	<10	57	<10	6	47
S07-34783	0.4	5.01	35	215	<5	5.14	<1	41	512	13	5.11	1.12	<10	7.10	1686	<1	0.99	272	860	20	10	<20	334	0.06	<10	153	<10	5	59
S07-34792	0.4	5.92	15	885	<5	2.01	<1	12	124	77	2.31	2.11	20	1.55	960	5	0.25	37	470	30	<5	<20	108	0.12	<10	77	<10	8	35
S07-34809	1.5	3.45	10	165	<5	3.01	3	12	208	63	3.29	1.45	20	1.39	985	26	0.08	61	730	34	<5	<20	129	0.08	<10	151	<10	5	200
S07-34818	1.4	4.47	35	165	<5	5.81	2	22	371	86	4.70	1.49	20	2.74	1694	22	0.35	171	760	48	10	<20	258	0.08	<10	155	<10	7	149
S07-34827	2.4	4.58	10	190	<5	2.33	3	17	243	71	4.31	1.83	20	1.14	772	26	0.20	71	1080	64	10	<20	116	0.12	<10	248	<10	7	257
S07-34844	0.4	7.07	10	355	<5	6.87	1	15	115	63	4.93	1.96	20	2.11	1209	12	1.31	31	2030	40	<5	<20	327	0.13	<10	201	<10	11	135
S07-34853	0.4	7.05	10	340	<5	3.85	1	14	156	82	3.65	2.26	20	1.57	802	14	1.10	41	800	30	<5	<20	224	0.12	<10	238	<10	9	122
S07-34862	0.2	4.50	10	285	<5	3.68	<1	11	133	68	2.60	1.41	20	1.26	1173	9	0.45	34	870	22	<5	<20	248	0.10	<10	146	<10	8	89
S07-34879	0.4	4.05	15	595	<5	2.21	<1	20	135	138	2.34	1.65	20	1.15	1750	8	0.44	54	380	30	<5	<20	99	0.09	<10	85	<10	6	88
S07-34888	1.0	7.17	10	330	<5	2.07	2	19	140	73	3.73	2.27	20	1.37	582	13	1.75	38	740	52	<5	<20	132	0.11	<10	230	<10	6	150
S07-34897	0.4	7.93	10	1070	<5	3.46	<1	13	73	62	3.13	2.28	10	1.79	794	1	2.43	20	940	35	<5	<20	244	0.14	<10	154	<10	7	72
S07-34914	0.6	3.53	45	310	<5	6.18	<1	32	493	62	4.17	1.53	10	4.30	2018	11	0.18	261	540	26	10	<20	592	0.04	<10	117	<10	7	100
S07-34923	0.2	6.02	10	1390	<5	0.88	<1	5	65	18	1.80	2.73	20	1.24	816	<1	0.23	11	300	24	<5	<20	70	0.12	<10	74	<10	6	41
S07-34739	0.2	4.56	250	275	<5	4.64	<1	34	857	2	4.23	1.78	<10	5.28	1651	<1	0.38	454	510	14	10	<20	350	0.03	<10	69	<10	6	120
S07-34774	0.8	3.56	50	350	<5	2.69	<1	23	277	103	2.67	1.04	10	2.60	1301	<1	0.62	114	580	32	<5	<20	217	0.08	<10	57	<10	6	51
S07-34809	1.2	3.82	10	120	<5	3.13	3	13	213	75	3.31	1.52	20	1.51	1085	28	0.10	70	810	32	5	<20	136	0.08	<10	156	<10	5	210
S07-34844	0.6	6.76	10	330	<5	5.62	1	16	122	65	4.91	2.09	30	2.02	1113	12	1.26	33	1830	44	<5	<20	304	0.12	<10	216	<10	9	138
S07-34879	0.6	4.05	15	590	<5	2.13	<1	21	131	142	2.37	1.72	20	1.21	1750	8	0.46	55	380	32	<5	<20	104	0.10	<10	92	<10	6	93
S07-34914	0.6	3.36	60	310	<5	5.69	<1	28	515	60	4.46	1.70	10	3.93	1905	13	0.17	251	580	30	5	<20	576	0.06	<10	121	<10	7	99

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La %	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
ird:	0.6	5.66	25	1220	<5	2.49	<1	15	59	36	3.98	1.40	30	1.39	2546	5	1.10	34	1690	66	<5	<20	275	0.32	<10	106	<10	27	201
	0.5	5.72	20	1315	<5	2.43	1	16	60	37	3.93	1.38	40	1.43	2502	5	1.14	35	1740	66	<5	<20	242	0.35	<10	116	<10	28	208
	0.5	5.69	20	1230	<5	2.49	1	16	58	39	4.01	1.42	30	1.39	2555	5	1.11	33	1770	60	<5	<20	237	0.35	<10	110	<10	27	199
	0.6	5.54	20	1205	<5	2.52	<1	15	57	39	3.97	1.52	40	1.32	2599	5	1.28	33	1660	58	<5	<20	264	0.31	<10	109	<10	27	201
	0.4	5.60	20	1230	<5	2.53	<1	15	59	39	3.93	1.34	30	1.36	2580	5	1.16	32	1740	60	<5	<20	260	0.31	<10	110	<10	28	200
	0.4	5.58	20	1250	<5	2.48	1	16	59	39	3.99	1.32	30	1.37	2569	5	1.14	34	1860	64	<5	<20	270	0.33	<10	112	<10	28	198

ICP: 4 ACID DIGEST/ICP-FINISH
 AG: 4 ACID DIGEST/AA-FINISH

Jutta Jealouse
 ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

as/td297bs



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2296

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

19-Mar-08


Attention: Bob Singh

No. of samples received: 95
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-161
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-06009	<0.03	<0.001
2	S07-06010	<0.03	<0.001
3	S07-06011	<0.03	<0.001
4	S07-06012	<0.03	<0.001
5	S07-06013	* 2.01	0.059
6	S07-06014	<0.03	<0.001
7	S07-06015	<0.03	<0.001
8	S07-06016	<0.03	<0.001
9	S07-06017	<0.03	<0.001
10	S07-06018	<0.03	<0.001
11	S07-06019	<0.03	<0.001
12	S07-06020	<0.03	<0.001
13	S07-06021	<0.03	<0.001
14	S07-06022	<0.03	<0.001
15	S07-06023	<0.03	<0.001
16	S07-06024	<0.03	<0.001
17	S07-06025	0.07	0.002
18	S07-06026	* <0.03	<0.001
19	S07-06027	<0.03	<0.001
20	S07-06028	0.15	0.004
21	S07-06029	<0.03	<0.001
22	S07-06030	<0.03	<0.001
23	S07-06031	<0.03	<0.001
24	S07-06032	<0.03	<0.001
25	S07-06033	<0.03	<0.001
26	S07-06034	<0.03	<0.001
27	S07-06035	<0.03	<0.001
28	S07-06036	<0.03	<0.001

* = 30g FA


ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	S07-06037	<0.03	<0.001
30	S07-06038	<0.03	<0.001
31	S07-06039	<0.03	<0.001
32	S07-06040	0.59	0.017
33	S07-06041	5.03	0.147
34	S07-06042	0.89	0.026
35	S07-06043	0.88	0.026
36	S07-06044	0.39	0.011
37	S07-06045	0.17	0.005
38	S07-06046	0.12	0.004
39	S07-06047	* 0.42	0.012
40	S07-06048	0.05	0.001
41	S07-06049	0.06	0.002
42	S07-06050	0.25	0.007
43	S07-06051	0.07	0.002
44	S07-06052	0.08	0.002
45	S07-06053	0.03	0.001
46	S07-06054	0.04	0.001
47	S07-06055	0.03	0.001
48	S07-06056	<0.03	<0.001
49	S07-06057	<0.03	<0.001
50	S07-06058	0.39	0.011
51	S07-06059	0.35	0.010
52	S07-06060	<0.03	<0.001
53	S07-06061	0.16	0.005
54	S07-06062	0.03	0.001
55	S07-06063	* <0.03	<0.001
56	S07-06064	<0.03	<0.001
57	S07-06065	<0.03	<0.001
58	S07-06066	0.05	0.002
59	S07-06067	<0.03	<0.001
60	S07-06068	0.06	0.002
61	S07-06069	<0.03	<0.001
62	S07-06070	<0.03	<0.001
63	S07-06071	<0.03	<0.001
64	S07-06072	<0.03	<0.001
65	S07-06073	0.05	0.001
66	S07-06074	0.07	0.002
67	S07-06075	0.06	0.002
68	S07-06076	1.33	0.039
69	S07-06077	* 6.79	0.198
70	S07-06078	0.85	0.025
71	S07-06079	0.21	0.006

* = 30g FA

ECC TECH LABORATORY LTD.

Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
72	S07-06080	0.03	0.001
73	S07-06081	<0.03	<0.001
74	S07-06082	<0.03	<0.001
75	S07-06083	<0.03	<0.001
76	S07-06084	0.22	0.006
77	S07-06085	0.11	0.003
78	S07-06086	0.37	0.011
79	S07-06087	<0.03	<0.001
80	S07-06088	<0.03	<0.001
81	S07-06089	<0.03	<0.001
82	S07-06090	<0.03	<0.001
83	S07-06091	<0.03	<0.001
84	S07-06092	<0.03	<0.001
85	S07-06093	1.25	0.037
86	S07-06094	0.46	0.013
87	S07-06095	0.03	0.001
88	S07-06096	0.14	0.004
89	S07-06097	<0.03	<0.001
90	S07-06098	<0.03	<0.001
91	S07-06099	<0.03	<0.001
92	S07-06100	<0.03	<0.001
93	S07-06101	0.11	0.003
94	S07-06102	<0.03	<0.001
95	S07-06103	0.04	0.001

QC DATA:

Resplit:

1	S07-06009	<0.03	<0.001
36	S07-06044	0.43	0.012
71	S07-06079	0.11	0.003

Standard:


OXI54	1.91	0.056
OXI54	1.84	0.054
OXI54	1.84	0.054
OXI54	1.86	0.054
OXI54	1.86	0.054
OXI54	1.88	0.055
OXI54	1.88	0.055
OXI54	1.85	0.054

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw

LS/07


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

TECH LABORATORY LTD.
 Dallas Drive
 OOPS, B.C.
 T4

ICP CERTIFICATE OF ANALYSIS 2007-2296

Skygold Ventures
 615 - 800 W. Pender Street
 Vancouver, BC
 V6B 2V6

: 250-573-5700
 : 250-573-4557

No. of samples received: 95
 Sample Type: Core
 Project: Spanish Mountain
 Shipment #: SMC-07-161
 Samples submitted by: Tasha Gainer

s in ppm unless otherwise reported

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
S07-06009	<0.2	5.67	220	410	<5	4.31	<1	36	766	32	4.76	1.15	10	1.79	1848	4	1.22	311	750	32	10	<20	233	0.08	<10	132	<10	7	101
S07-06010	<0.2	5.83	120	380	<5	4.88	<1	34	905	30	4.98	0.89	<10	3.08	1759	2	1.30	301	790	28	10	<20	200	0.05	<10	151	<10	5	114
S07-06011	<0.2	5.20	100	200	<5	4.22	<1	35	708	71	4.62	0.69	<10	3.45	1573	1	1.10	299	870	26	5	<20	196	0.06	<10	148	<10	6	79
S07-06012	<0.2	4.70	75	145	<5	5.84	<1	49	864	34	4.68	0.55	<10	6.47	1821	<1	0.94	448	720	26	10	<20	206	0.04	<10	115	<10	5	79
S07-06013	4.7	4.55	105	320	<5	0.41	<1	11	38	637	4.93	2.22	10	1.78	399	8	0.24	26	430	96	50	<20	66	0.28	<10	54	<10	11	669
S07-06014	<0.2	6.24	70	400	<5	5.55	<1	26	425	28	4.74	1.03	<10	3.40	1901	<1	1.29	146	880	26	<5	<20	263	0.09	<10	137	<10	6	62
S07-06015	0.2	5.82	25	1385	<5	2.37	<1	11	116	32	2.17	1.38	10	2.10	1661	<1	0.51	62	570	54	<5	<20	131	0.13	<10	40	<10	8	62
S07-06016	<0.2	5.20	80	890	<5	3.75	<1	23	463	6	2.83	1.50	10	2.68	2200	<1	0.43	191	540	20	<5	<20	225	0.08	<10	60	<10	7	82
S07-06017	<0.2	4.97	185	430	<5	3.34	<1	38	392	53	3.99	1.66	10	2.51	1923	<1	0.36	240	850	26	<5	<20	209	0.09	<10	112	<10	6	92
S07-06018	<0.2	5.33	20	1155	<5	1.27	<1	8	89	14	2.10	1.39	20	1.65	1221	<1	0.18	29	280	26	<5	<20	70	0.10	<10	54	<10	8	50
S07-06019	0.4	5.73	40	1070	<5	1.29	<1	9	71	43	2.10	1.41	20	1.38	1059	<1	0.34	35	340	30	<5	<20	79	0.11	<10	77	<10	9	59
S07-06020	0.2	5.53	115	375	<5	2.57	<1	17	272	4	2.48	1.53	20	2.92	778	<1	0.52	146	440	18	<5	<20	169	0.08	<10	56	<10	8	73
S07-06021	0.2	4.74	60	185	<5	3.78	<1	36	593	28	4.94	1.41	<10	7.43	1559	<1	0.55	249	760	22	10	<20	173	0.06	<10	144	<10	5	62
S07-06022	0.4	4.12	85	115	<5	5.97	<1	47	883	68	4.64	1.31	<10	7.52	2074	<1	0.45	410	590	18	10	<20	208	0.03	<10	120	<10	6	83
S07-06023	0.4	4.96	75	450	<5	3.89	<1	38	784	58	4.81	1.46	<10	6.31	2622	<1	0.43	279	590	34	10	<20	213	0.06	<10	204	<10	5	126
S07-06024	0.4	5.28	20	165	<5	2.91	2	19	249	94	3.40	1.79	20	1.95	757	17	0.54	72	1320	30	<5	<20	149	0.09	<10	207	<10	8	153
S07-06025	0.4	6.24	10	265	<5	2.86	1	11	151	53	2.46	1.59	10	1.70	654	8	1.17	27	770	22	<5	<20	165	0.10	<10	151	<10	8	104
S07-06026	0.2	7.08	<5	485	<5	2.78	<1	11	42	37	5.45	0.90	10	1.33	782	3	2.92	27	790	24	<5	<20	369	0.36	<10	115	<10	18	58
S07-06027	0.2	6.71	<5	615	<5	2.73	<1	6	128	45	2.39	1.70	20	1.75	633	2	1.39	18	840	22	<5	<20	167	0.12	<10	124	<10	8	92
S07-06028	0.4	6.64	10	450	<5	2.36	<1	10	116	55	2.75	1.72	10	1.97	635	3	1.66	20	750	26	<5	<20	165	0.11	<10	127	<10	7	79
S07-06029	0.2	6.25	10	210	<5	2.45	<1	11	107	48	2.91	1.82	20	1.71	626	3	1.43	23	670	26	<5	<20	160	0.10	<10	125	<10	7	94
S07-06030	0.4	5.29	10	310	<5	2.72	<1	10	154	47	2.51	1.48	10	1.63	639	3	1.35	23	520	20	<5	<20	166	0.09	<10	118	<10	6	86
S07-06031	0.2	5.30	<5	460	<5	3.34	<1	7	130	54	2.45	1.64	10	1.77	777	3	1.62	21	540	20	<5	<20	203	0.10	<10	139	<10	7	84
S07-06032	<0.2	5.34	<5	600	<5	1.47	1	10	99	45	2.44	1.51	10	1.42	435	6	1.89	25	520	18	<5	<20	126	0.11	<10	148	<10	5	126
S07-06033	<0.2	4.91	10	385	<5	2.06	1	9	106	49	2.38	1.30	10	1.53	589	5	1.69	25	460	20	<5	<20	145	0.11	<10	130	<10	5	120

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn	
S07-06034	0.4	5.29	<5	410	<5	1.34	1	8	89	46	2.40	1.34	10	1.30	418	8	2.12	20	480	18	<5	<20	126	0.12	<10	150	<10	5	103
S07-06035	0.2	5.56	10	420	<5	1.38	1	10	108	49	2.51	1.44	10	1.43	440	8	2.17	25	530	22	<5	<20	128	0.13	<10	158	<10	5	119
S07-06036	0.4	5.32	10	205	<5	1.87	1	12	152	55	2.48	1.44	10	1.32	579	7	1.72	27	510	22	<5	<20	156	0.14	<10	153	<10	6	120
S07-06037	0.2	5.54	<5	485	<5	1.51	1	7	121	46	2.38	1.52	10	1.59	456	3	1.84	22	520	20	<5	<20	127	0.13	<10	149	<10	5	112
S07-06038	0.4	5.49	10	515	<5	1.73	1	10	97	43	2.52	1.66	10	1.59	495	3	1.79	24	530	18	<5	<20	133	0.13	<10	139	<10	5	118
S07-06039	0.2	5.66	10	660	<5	2.91	<1	10	126	49	2.50	1.81	10	1.64	598	2	0.91	21	600	24	<5	<20	159	0.11	<10	136	<10	8	88
S07-06040	0.2	5.33	15	220	<5	2.93	1	13	183	56	3.38	1.90	10	1.36	626	25	0.49	40	990	26	<5	<20	135	0.11	<10	161	<10	7	114
S07-06041	1.2	6.08	15	240	<5	2.23	1	19	187	86	5.33	2.40	10	1.18	491	82	0.57	69	1570	30	<5	<20	134	0.13	<10	197	<10	8	116
S07-06042	0.4	6.19	10	240	<5	3.08	1	11	226	86	2.77	2.08	20	1.59	776	14	0.55	30	690	26	<5	<20	190	0.12	<10	186	<10	8	113
S07-06043	0.6	6.66	15	125	<5	2.90	<1	14	180	75	3.57	2.49	20	1.46	627	3	0.88	26	650	30	<5	<20	180	0.12	<10	118	<10	7	69
S07-06044	0.2	6.82	20	290	<5	3.38	<1	12	136	62	2.67	2.05	20	1.69	850	2	1.03	30	690	34	<5	<20	194	0.14	<10	112	<10	7	88
S07-06045	0.4	7.48	5	815	<5	3.08	<1	8	75	66	2.68	2.14	20	1.79	953	<1	0.83	10	970	42	<5	<20	195	0.16	<10	100	<10	9	70
S07-06046	0.4	7.26	5	330	<5	3.70	<1	15	105	70	4.20	2.08	20	1.90	1122	<1	1.61	17	1180	28	<5	<20	228	0.17	<10	123	<10	8	90
S07-06047	0.8	4.92	110	240	<5	0.23	<1	8	24	32	3.15	3.30	10	0.34	174	3	0.12	16	500	20	40	<20	55	0.37	<10	69	<10	11	55
S07-06048	<0.2	6.97	10	505	<5	3.00	<1	13	132	74	4.00	1.89	20	1.68	1034	2	1.84	20	770	30	<5	<20	202	0.15	<10	126	<10	6	70
S07-06049	<0.2	7.12	<5	705	<5	3.33	<1	17	130	52	4.38	1.88	20	1.83	1150	<1	2.16	19	1040	34	<5	<20	244	0.15	<10	147	<10	6	84
S07-06050	0.2	7.44	10	315	<5	4.02	<1	17	132	87	4.62	2.15	20	1.71	1097	<1	1.51	20	970	32	<5	<20	233	0.16	<10	157	<10	6	64
S07-06051	<0.2	8.39	10	650	<5	4.12	<1	19	71	60	4.97	2.05	10	2.19	1268	4	1.21	20	900	38	<5	<20	251	0.17	<10	191	<10	6	68
S07-06052	0.2	7.29	10	575	<5	3.71	<1	16	55	61	4.13	2.15	10	1.52	948	1	1.96	16	870	32	<5	<20	219	0.16	<10	138	<10	5	78
S07-06053	0.2	6.94	10	700	<5	2.83	2	9	91	54	2.77	2.47	20	0.84	679	4	1.46	16	710	26	<5	<20	162	0.14	<10	123	<10	7	109
S07-06054	<0.2	7.96	<5	1100	<5	3.51	<1	11	27	68	3.60	2.16	20	1.52	1115	7	0.91	13	1060	34	<5	<20	199	0.15	<10	113	<10	7	76
S07-06055	<0.2	7.88	<5	770	<5	3.70	<1	14	43	63	3.83	2.52	20	1.64	1085	<1	1.61	22	1240	34	<5	<20	235	0.14	<10	125	<10	6	89
S07-06056	<0.2	8.07	5	725	<5	3.22	<1	18	86	68	4.32	2.43	20	1.78	1161	7	1.91	21	980	38	<5	<20	253	0.16	<10	149	<10	5	97
S07-06057	0.2	7.33	<5	525	<5	3.97	<1	16	87	70	3.98	2.18	10	1.71	1214	<1	2.36	23	760	34	<5	<20	201	0.14	<10	147	<10	5	75
S07-06058	0.4	8.11	10	245	<5	5.06	<1	25	106	115	5.20	2.33	10	1.90	1298	2	1.66	33	800	44	<5	<20	242	0.13	<10	204	<10	5	60
S07-06059	0.2	8.64	<5	750	<5	5.48	<1	23	90	93	5.41	2.57	10	2.40	1712	<1	0.99	28	1110	50	<5	<20	245	0.17	<10	206	<10	6	74
S07-06060	<0.2	8.68	5	565	<5	4.63	<1	25	46	73	5.10	2.84	10	2.26	1547	<1	1.16	24	870	40	<5	<20	214	0.18	<10	216	<10	3	77
S07-06061	0.2	8.09	5	465	<5	3.85	<1	17	58	55	4.33	2.44	10	1.90	1340	<1	1.90	28	680	36	<5	<20	214	0.18	<10	181	<10	4	64
S07-06062	<0.2	8.66	10	655	<5	5.04	<1	19	74	55	4.86	2.67	<10	2.39	1748	<1	1.87	25	670	38	<5	<20	314	0.17	<10	196	<10	4	77
S07-06063	<0.2	0.26	<5	65	<5	>10	<1	1	3	<1	0.57	0.14	<10	>10	200	<1	0.05	4	220	<2	<5	<20	56	<0.01	<10	5	<10	<1	20
S07-06064	0.2	7.57	10	430	<5	5.75	<1	19	79	151	4.60	1.56	10	2.01	1818	<1	2.54	31	740	36	<5	<20	371	0.19	<10	209	<10	6	78
S07-06065	<0.2	7.80	<5	580	<5	2.09	<1	14	67	53	3.45	1.99	20	1.63	888	<1	2.58	25	730	30	<5	<20	256	0.20	<10	120	<10	6	84
S07-06066	0.2	8.34	10	555	<5	5.79	<1	25	69	113	4.45	2.16	10	2.28	1887	<1	2.20	30	810	34	<5	<20	443	0.17	<10	210	<10	4	59
S07-06067	<0.2	8.62	15	740	<5	4.80	<1	25	42	76	5.31	2.45	<10	2.62	1773	<1	1.58	34	800	32	<5	<20	257	0.18	<10	217	<10	4	91
S07-06068	<0.2	8.46	10	750	<5	4.01	<1	18	52	51	4.15	2.32	20	1.91	1279	<1	1.90	25	620	34	<5	<20	240	0.20	<10	150	<10	5	53
S07-06069	<0.2	7.45	5	485	<5	5.19	<1	12	79	65	3.10	1.85	20	1.72	1252	<1	3.07	19	1700	30	<5	<20	324	0.22	<10	139	<10	9	52
S07-06070	<0.2	8.17	15	665	<5	4.26	<1	20	71	82	4.83	2.41	10	2.41	1274	<1	1.64	34	720	40	<5	<20	269	0.19	<10	170	<10	4	92
S07-06071	<0.2	7.86	10	645	<5	4.16	<1	20	96	79	4.58	2.11	10	2.33	1227	<1	1.68	31	950	36	<5	<20	269	0.17	<10	163	<10	5	74
S07-06072	0.2	7.47	10	635	<5	3.76	<1	15	76	66	3.62	2.13	10	1.89	1001	<1	1.88	24	580	26	<5	<20	246	0.16	<10	139	<10	4	57
S07-06073	<0.2	>10	10	1125	<5	6.15	<1	18	58	21	4.65	2.16	10	2.39	1679	<1	1.89	24	1340	40	<5	<20	519	0.28	<10	211	<10	6	48

Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Li	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
S07-06074	<0.2	9.03	10	705	<5	5.61	<1	15	74	35	4.18	2.24	10	1.83	1427	<1	2.53	19	1080	32	<5	<20	395	0.27	<10	156	<10	6	50
S07-06075	0.2	8.39	10	600	<5	5.76	<1	15	118	70	4.27	2.25	10	1.88	1466	<1	2.43	18	970	38	<5	<20	308	0.26	<10	160	<10	6	76
S07-06076	4.0	8.65	10	435	<5	4.10	1	17	97	124	4.12	2.48	10	1.69	1028	<1	2.22	18	870	2692	<5	<20	235	0.26	<10	163	<10	6	96
S07-06077	6.6	3.94	195	310	<5	0.44	<1	7	40	58	3.62	2.99	10	0.26	235	6	0.54	23	430	30	65	<20	90	0.30	<10	53	<10	10	52
S07-06078	0.4	9.38	15	450	<5	4.13	1	17	92	118	4.89	2.49	10	1.94	1114	<1	2.01	22	1020	132	<5	<20	234	0.27	<10	182	<10	7	152
S07-06079	0.2	8.33	<5	360	<5	5.31	<1	14	94	80	4.01	2.43	10	2.05	1260	<1	2.44	17	970	44	<5	<20	317	0.28	<10	158	<10	9	71
S07-06080	<0.2	8.81	<5	515	<5	3.81	<1	12	80	45	3.97	2.27	20	1.71	1000	<1	2.79	15	920	34	<5	<20	324	0.28	<10	140	<10	9	64
S07-06081	0.2	8.87	5	685	<5	4.06	<1	19	96	70	4.72	2.46	10	2.19	1071	<1	2.90	24	940	32	<5	<20	359	0.28	<10	194	<10	5	78
S07-06082	0.2	7.19	5	545	<5	3.86	<1	13	162	54	3.07	2.20	<10	1.52	819	<1	2.16	18	730	26	<5	<20	318	0.21	<10	173	<10	6	39
S07-06083	2.0	8.30	5	500	<5	4.22	2	17	160	76	4.56	2.17	10	2.09	1208	<1	1.97	23	850	486	<5	<20	340	0.25	<10	190	<10	5	128
S07-06084	0.2	8.55	5	330	<5	3.68	<1	17	80	86	4.58	2.24	10	1.94	1072	<1	3.09	21	870	40	<5	<20	261	0.26	<10	195	<10	5	93
S07-06085	1.6	8.95	<5	585	<5	4.25	<1	18	87	112	4.82	2.17	10	2.14	1302	<1	2.33	21	930	568	<5	<20	254	0.27	<10	219	<10	5	118
S07-06086	0.2	8.62	<5	625	<5	5.52	<1	19	83	61	4.95	2.38	<10	2.39	1514	<1	1.65	23	940	44	<5	<20	286	0.23	<10	245	<10	6	99
S07-06087	<0.2	9.25	5	715	<5	5.00	<1	21	89	54	4.98	2.72	<10	2.46	1375	<1	1.97	24	860	34	<5	<20	304	0.24	<10	251	<10	6	54
S07-06088	<0.2	8.74	<5	680	<5	4.80	<1	19	70	47	4.73	2.94	<10	2.33	1214	<1	1.91	23	780	36	<5	<20	298	0.24	<10	226	<10	5	60
S07-06089	<0.2	8.51	10	830	<5	5.00	<1	17	117	53	4.46	2.45	10	2.15	1304	<1	1.00	17	860	32	<5	<20	341	0.28	<10	218	<10	7	45
S07-06090	0.2	6.60	<5	835	<5	3.31	<1	8	165	40	2.27	2.50	20	0.89	645	<1	1.08	9	600	28	<5	<20	311	0.18	<10	76	<10	7	42
S07-06091	0.2	6.87	10	540	<5	4.36	1	16	120	62	3.14	2.03	10	1.56	968	<1	2.55	23	1030	54	<5	<20	413	0.21	<10	159	<10	7	111
S07-06092	<0.2	8.11	10	820	<5	5.71	<1	18	101	48	4.31	2.06	10	2.09	1383	<1	1.65	25	1100	30	<5	<20	393	0.26	<10	212	<10	7	44
S07-06093	1.0	8.36	15	390	<5	5.38	<1	21	136	166	5.17	2.54	20	2.13	1397	<1	1.32	17	1760	48	<5	<20	386	0.38	<10	254	<10	12	70
S07-06094	0.6	7.80	5	585	<5	5.27	<1	20	93	263	5.52	2.62	20	1.96	1489	2	1.72	14	2200	34	<5	<20	379	0.39	<10	253	<10	13	102
S07-06095	0.4	7.69	5	575	<5	4.84	<1	20	77	188	5.25	2.24	20	1.86	1608	<1	2.43	12	2110	32	<5	<20	417	0.46	<10	259	<10	11	66
S07-06096	0.2	7.25	10	620	<5	3.73	<1	16	81	84	4.25	2.23	20	1.62	1112	<1	1.48	13	1650	34	<5	<20	355	0.32	<10	154	<10	10	60
S07-06097	<0.2	7.42	<5	630	<5	4.78	<1	9	81	18	3.62	2.29	20	1.50	1173	<1	2.38	10	1130	30	<5	<20	358	0.31	<10	109	<10	10	75
S07-06098	<0.2	7.83	<5	615	<5	4.16	<1	11	112	40	3.96	2.22	20	1.44	1060	<1	2.64	15	930	30	<5	<20	324	0.28	<10	121	<10	7	67
S07-06099	<0.2	7.96	<5	655	<5	4.37	<1	12	74	45	3.38	2.62	20	1.38	953	<1	2.08	12	580	30	<5	<20	316	0.25	<10	113	<10	7	63
S07-06100	<0.2	8.40	5	580	<5	4.15	<1	20	104	40	4.82	2.15	<10	2.05	1195	<1	3.44	21	810	32	<5	<20	447	0.29	<10	228	<10	5	67
S07-06101	0.2	8.20	10	555	<5	4.44	<1	19	79	60	4.67	1.95	<10	2.01	1152	<1	3.92	23	750	32	<5	<20	614	0.28	<10	204	<10	5	58
S07-06102	<0.2	7.95	5	505	<5	4.40	<1	17	81	44	4.25	1.73	<10	1.85	1075	<1	3.96	19	670	32	<5	<20	610	0.26	<10	185	<10	5	65
S07-06103	0.2	7.94	<5	635	<5	3.74	<1	19	82	122	4.51	2.13	<10	1.83	1051	<1	3.46	17	740	32	<5	<20	469	0.27	<10	176	<10	4	65

ITA:

it:


S07-06009	<0.2	5.57	220	405	<5	4.15	<1	35	763	32	4.73	1.11	<10	1.78	1820	3	1.18	307	740	30	10	<20	228	0.08	<10	129	<10	7	99
S07-06018	<0.2	5.13	20	1145	<5	1.21	<1	7	85	15	2.03	1.40	20	1.66	1161	<1	0.18	27	270	26	<5	<20	70	0.09	<10	53	<10	8	50
S07-06027	0.2	6.84	<5	625	<5	2.82	<1	7	136	46	2.39	1.73	20	1.78	625	2	1.43	17	830	26	<5	<20	168	0.12	<10	125	<10	8	94
S07-06044	<0.2	6.81	20	275	<5	3.41	<1	13	134	64	2.80	2.17	20	1.69	824	2	1.06	29	670	32	<5	<20	193	0.14	<10	111	<10	7	89
S07-06053	0.4	7.04	5	660	<5	2.93	2	9	97	59	2.59	2.62	20	0.87	704	4	1.51	17	730	30	<5	<20	170	0.14	<10	126	<10	7	118
S07-06062	<0.2	8.53	10	640	<5	5.07	<1	20	69	54	4.85	2.49	<10	2.38	1761	<1	1.91	25	690	38	<5	<20	305	0.19	<10	194	<10	4	84
S07-06079	<0.2	8.02	5	350	<5	5.20	<1	14	93	78	4.06	2.52	10	2.00	1209	<1	2.34	16	940	46	<5	<20	313	0.26	<10	159	<10	8	66
S07-06088	<0.2	9.07	10	695	<5	4.97	<1	19	73	51	4.92	3.18	<10	2.37	1245	<1	2.00	23	810	36	<5	<20	303	0.25	<10	231	<10	7	62

it:

S07-06009	<0.2	5.45	215	395	<5	4.11	<1	35	761	32	4.70	1.09	<10	1.83	1815	4	1.17	307	710	30	10	<20	225	0.08	<10	127	<10	7	95
S07-06044	0.4	6.94	20	280	<5	3.68	<1	12	130	65	2.43	2.05	20	1.68	822	2	1.07	29	690	34	<5	<20	196	0.15	<10	114	<10	8	89
S07-06079	0.2	8.27	5	375	<5	5.54	<1	16	97	90	4.22	2.76	10	2.04	1276	<1	2.33	18	960	38	<5	<20	318	0.26	<10	168	<10	9	68


Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Li	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
ird:	0.5	5.68	20	1265	<5	2.40	1	16	58	39	3.98	1.55	40	1.41	2551	5	1.41	33	1870	62	<5	<20	330	0.32	<10	101	<10	28	202
	0.4	5.76	20	1265	<5	2.37	<1	15	61	38	3.96	1.63	40	1.43	2643	5	1.41	33	1780	64	<5	<20	334	0.35	<10	112	<10	29	196
	0.5	5.66	20	1275	<5	2.35	1	15	60	41	3.92	1.61	40	1.39	2620	5	1.44	34	1750	62	<5	<20	335	0.36	<10	107	<10	29	190

ACID DIGEST/ICP-FINISH
 ACID DIGEST/AA-FINISH



 ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

3s
 7



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2292

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

13-Mar-08

Attention: Bob Singh

No. of samples received: 61
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-163
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-06104	<0.03	<0.001
2	S07-06105	<0.03	<0.001
3	S07-06106	<0.03	<0.001
4	S07-06107	<0.03	<0.001
5	S07-06108	<0.03	<0.001
6	S07-06109	<0.03	<0.001
7	S07-06110	<0.03	<0.001
8	S07-06111	<0.03	<0.001
9	S07-06112	0.11	0.003
10	S07-06113	0.06	0.002
11	S07-06114	0.16	0.005
12	S07-06115	0.03	0.001
13	S07-06116	0.22	0.006
14	S07-06117	0.05	0.001
15	S07-06118	2.03	0.059
16	S07-06119	0.07	0.002
17	S07-06120	0.10	0.003
18	S07-06121	0.03	0.001
19	S07-06122	<0.03	<0.001
20	S07-06123	0.09	0.003
21	S07-06124	<0.03	<0.001
22	S07-06125	<0.03	<0.001
23	S07-06126	0.06	0.002
24	S07-06127	0.56	0.016
25	S07-06128	<0.03	<0.001
26	S07-06129	0.17	0.005
27	S07-06130	<0.03	<0.001
28	S07-06131	<0.03	<0.001

* = 30g FA

ECO TECH LABORATORY LTD.

Julia Jealouse
R.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	S07-06132	<0.03	<0.001
30	S07-06133	<0.03	<0.001
31	S07-06134	<0.03	<0.001
32	S07-06135	<0.03	<0.001
33	S07-06136	0.11	0.003
34	S07-06137	0.21	0.006
35	S07-06138	<0.03	<0.001
36	S07-06139	<0.03	<0.001
37	S07-06140	14.3	0.417
38	S07-06141	* 0.43	0.013
39	S07-06142	0.06	0.002
40	S07-06143	0.06	0.002
41	S07-06144	0.31	0.009
42	S07-06145	2.94	0.086
43	S07-06146	<0.03	<0.001
44	S07-06147	<0.03	<0.001
45	S07-06148	0.03	0.001
46	S07-06149	<0.03	<0.001
47	S07-06150	<0.03	<0.001
48	S07-06151	<0.03	<0.001
49	S07-06152	* <0.03	<0.001
50	S07-06153	0.09	0.002
51	S07-06154	0.06	0.002
52	S07-06155	<0.03	<0.001
53	S07-06156	<0.03	<0.001
54	S07-06157	0.14	0.004
55	S07-06158	0.22	0.006
56	S07-06159	0.21	0.006
57	S07-06160	0.09	0.002
58	S07-06161	<0.03	<0.001
59	S07-06162	0.04	0.001
60	S07-06163	0.33	0.010
61	S07-06164	0.08	0.002

QC DATA:**Resplit:**

1	S07-06104	<0.03	<0.001
36	S07-06139	<0.03	<0.001

Standard:

OXI54	1.86	0.054
OXI54	1.88	0.055
OXI54	1.84	0.054
OXI54	1.90	0.055
OXI54	1.86	0.054

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw
XI S/07


 ECO TECH LABORATORY LTD.

Jutta Jealous

13-Mar-08

ECO TECH LABORATORY LTD.

10041 Dallas Drive
KAMLOOPS, B.C.
 V2C 6T4

Phone: 250-573-5700
 Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2007-2292

Skygold Ventures

615 - 800 W. Pender Street
Vancouver, BC
 V6B 2V6

No. of samples received: 61
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-163
Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y
1	S07-06104	<0.2	8.67	25	620	<5	3.18	<1	19	159	69	4.99	1.70	<10	1.60	1107	<1	2.97	17	780	30	<5	<20	405	0.30	<10	186	<10	6
2	S07-06105	<0.2	7.22	15	505	<5	4.13	<1	11	68	69	3.15	1.57	20	1.02	872	<1	2.01	9	780	26	<5	<20	380	0.21	<10	79	<10	10
3	S07-06106	0.4	6.48	15	670	<5	2.28	<1	4	107	49	1.84	1.65	20	0.60	509	<1	1.54	6	710	26	<5	<20	239	0.14	<10	48	<10	10
4	S07-06107	0.6	7.16	15	880	<5	3.24	<1	7	82	24	2.67	2.04	20	0.86	662	<1	1.30	8	500	24	<5	<20	283	0.16	<10	61	<10	10
5	S07-06108	<0.2	0.16	<5	20	<5	>10	<1	<1	5	2	0.53	0.05	<10	>10	185	<1	0.02	3	170	2	<5	<20	40	<0.01	<10	3	<10	<1
6	S07-06109	<0.2	7.51	10	1060	<5	3.72	<1	5	50	19	2.14	1.89	20	0.73	642	<1	1.60	6	420	26	<5	<20	410	0.14	<10	59	<10	11
7	S07-06110	<0.2	7.48	15	865	<5	2.80	<1	5	78	8	2.06	1.57	20	0.73	603	<1	1.75	6	400	26	<5	<20	392	0.16	<10	54	<10	12
8	S07-06111	0.2	5.57	10	1105	<5	3.23	<1	5	77	58	2.24	1.05	10	0.63	675	<1	1.45	7	440	22	<5	<20	330	0.17	<10	54	<10	8
9	S07-06112	<0.2	7.11	15	1020	<5	3.63	<1	6	65	65	2.91	2.36	20	0.96	810	<1	0.81	7	810	24	<5	<20	227	0.18	<10	64	<10	10
10	S07-06113	<0.2	6.80	10	890	<5	3.06	<1	7	68	40	2.58	2.30	20	0.85	699	<1	0.94	7	460	26	<5	<20	243	0.17	<10	50	<10	10
11	S07-06114	0.2	7.09	15	955	<5	3.54	<1	7	76	41	2.68	2.34	20	0.87	718	<1	0.96	7	460	28	<5	<20	252	0.17	<10	51	<10	10
12	S07-06115	<0.2	7.26	15	795	<5	2.73	<1	5	64	15	2.24	1.89	20	0.77	593	<1	1.88	6	430	24	<5	<20	290	0.16	<10	64	<10	9
13	S07-06116	<0.2	7.76	20	555	<5	3.83	<1	18	77	75	3.93	1.55	10	1.42	1012	<1	2.76	14	750	28	<5	<20	440	0.24	<10	159	<10	6
14	S07-06117	<0.2	7.78	20	770	<5	3.63	<1	19	105	88	4.90	1.82	<10	1.63	1041	<1	2.39	17	590	30	<5	<20	394	0.22	<10	189	<10	4
15	S07-06118	4.5	4.57	115	315	<5	0.50	1	12	36	619	5.19	2.16	10	1.65	392	10	0.27	24	460	90	45	<20	60	0.29	<10	59	<10	11
16	S07-06119	0.2	8.02	20	920	<5	3.63	2	21	98	166	5.41	1.97	<10	1.84	1140	<1	2.25	16	760	28	<5	<20	390	0.22	<10	203	<10	5
17	S07-06120	<0.2	8.49	25	700	<5	3.78	<1	21	108	71	5.33	1.39	<10	1.72	1112	<1	3.36	17	710	32	<5	<20	501	0.23	<10	184	<10	5
18	S07-06121	<0.2	6.94	15	725	<5	2.79	<1	5	95	13	2.10	1.53	20	0.82	633	<1	2.48	6	420	22	<5	<20	344	0.14	<10	53	<10	8
19	S07-06122	<0.2	7.09	15	995	<5	3.10	<1	6	81	25	2.45	2.27	20	0.94	665	<1	1.14	7	480	26	<5	<20	252	0.17	<10	50	<10	10
20	S07-06123	0.2	7.15	15	760	<5	2.84	<1	8	78	70	2.38	1.68	20	0.83	641	<1	2.22	7	450	28	<5	<20	299	0.16	<10	75	<10	8
21	S07-06124	<0.2	7.43	20	790	<5	3.59	<1	14	73	53	4.05	1.69	10	1.39	959	<1	2.30	13	690	26	<5	<20	344	0.24	<10	121	<10	8
22	S07-06125	<0.2	6.62	15	620	<5	2.78	<1	13	53	60	3.98	1.32	10	1.26	804	<1	2.70	12	660	24	<5	<20	267	0.23	<10	120	<10	6
23	S07-06126	0.2	7.38	20	540	<5	3.12	<1	14	94	67	4.04	1.08	10	1.31	998	<1	3.08	12	700	26	<5	<20	350	0.25	<10	116	<10	7
24	S07-06127	<0.2	8.48	20	950	<5	3.33	<1	20	49	53	5.47	1.83	<10	1.69	1184	<1	2.52	14	820	28	<5	<20	341	0.30	<10	185	<10	5
25	S07-06128	<0.2	7.87	25	845	<5	3.95	<1	26	67	73	5.47	1.72	<10	1.97	1208	<1	1.89	23	770	28	<5	<20	310	0.28	<10	207	<10	5

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y
26	S07-06129	0.2	7.55	20	520	<5	4.41	<1	24	89	67	5.48	1.38	<10	2.36	1118	<1	2.28	30	790	28	<5	<20	297	0.25	<10	219	<10	7
27	S07-06130	0.4	7.44	20	325	<5	3.99	<1	22	75	115	5.46	0.50	10	2.10	1029	<1	2.99	26	890	24	<5	<20	349	0.30	<10	232	<10	5
28	S07-06131	<0.2	7.83	20	265	<5	4.26	<1	22	77	110	5.15	0.48	10	2.01	1029	<1	3.16	23	860	26	<5	<20	363	0.32	<10	215	<10	6
29	S07-06132	<0.2	7.72	25	380	<5	3.82	<1	26	89	91	5.87	0.54	10	2.08	1040	<1	3.16	36	900	26	<5	<20	336	0.34	<10	261	<10	6
30	S07-06133	<0.2	7.78	25	320	<5	4.22	<1	22	74	119	5.70	0.73	<10	2.09	1128	<1	2.91	23	930	28	<5	<20	378	0.29	<10	243	<10	6
31	S07-06134	0.4	8.09	30	465	<5	4.88	<1	27	88	120	6.13	1.09	<10	2.30	1242	<1	2.83	26	820	30	<5	<20	384	0.33	<10	293	<10	6
32	S07-06135	<0.2	8.17	25	705	<5	4.35	<1	24	77	94	5.52	1.48	<10	2.23	1108	<1	2.67	24	870	30	<5	<20	335	0.26	<10	267	<10	5
33	S07-06136	0.4	7.77	25	630	<5	3.80	<1	25	104	105	5.63	1.71	10	2.12	1120	<1	2.24	27	880	30	<5	<20	269	0.29	<10	265	<10	6
34	S07-06137	0.4	7.85	25	570	<5	3.78	<1	24	99	158	5.69	1.60	<10	2.10	1078	<1	2.43	30	900	40	<5	<20	283	0.29	<10	270	<10	6
35	S07-06138	0.2	7.83	30	565	<5	3.84	<1	24	99	126	5.57	1.41	<10	2.17	1114	<1	2.72	31	930	30	<5	<20	300	0.29	<10	217	<10	5
36	S07-06139	<0.2	8.01	15	710	<5	3.72	<1	26	93	131	6.07	1.60	<10	2.38	1173	<1	2.23	29	750	34	<5	<20	316	0.25	<10	268	<10	5
37	S07-06140	2.0	7.71	10	505	<5	3.75	<1	16	103	865	5.01	1.18	<10	1.79	988	<1	2.96	23	770	36	<5	<20	314	0.29	<10	190	<10	8
38	S07-06141	0.8	5.73	85	385	<5	0.26	<1	9	25	34	3.25	4.40	10	0.33	171	4	0.09	15	440	22	35	<20	45	0.40	<10	71	<10	13
39	S07-06142	0.2	7.61	15	550	<5	3.39	<1	19	76	104	5.19	1.24	10	1.83	1016	<1	2.76	26	1030	38	<5	<20	331	0.31	<10	205	<10	10
40	S07-06143	<0.2	7.33	15	625	<5	4.21	<1	25	96	144	5.58	1.23	10	2.07	987	1	2.45	31	1130	32	<5	<20	381	0.29	<10	247	<10	9
41	S07-06144	0.6	7.62	25	485	<5	5.02	<1	22	105	102	5.35	1.00	10	2.07	1100	<1	3.02	29	1180	44	<5	<20	540	0.31	<10	221	<10	10
42	S07-06145	0.2	7.49	15	545	<5	4.49	<1	25	137	158	5.92	1.22	10	2.12	1091	1	2.68	36	1100	40	<5	<20	418	0.26	<10	253	<10	8
43	S07-06146	0.2	7.64	15	410	<5	4.06	<1	27	97	62	6.16	0.99	10	2.29	1122	<1	2.56	36	1010	38	<5	<20	414	0.34	<10	266	<10	8
44	S07-06147	<0.2	8.12	30	730	<5	4.41	<1	28	115	64	6.69	1.19	10	2.71	1186	<1	1.96	47	1030	34	<5	<20	405	0.27	<10	275	<10	8
45	S07-06148	<0.2	8.01	20	520	<5	4.21	<1	25	105	78	5.58	0.73	10	2.36	1079	<1	2.89	36	1020	32	<5	<20	418	0.31	<10	228	<10	9
46	S07-06149	<0.2	7.16	30	465	<5	4.27	<1	35	327	56	6.76	0.85	10	3.77	1271	<1	1.66	103	1030	32	<5	<20	395	0.15	<10	264	<10	8
47	S07-06150	<0.2	7.15	20	780	<5	3.93	<1	30	123	75	5.85	1.41	<10	2.89	1227	<1	2.11	43	940	28	<5	<20	410	0.18	<10	253	<10	8
48	S07-06151	0.2	7.42	20	755	<5	4.06	<1	24	85	76	5.41	1.01	<10	2.49	1112	<1	2.51	36	880	30	<5	<20	413	0.23	<10	228	<10	9
49	S07-06152	<0.2	0.24	<5	25	<5	>10	<1	<1	<1	5	0.63	0.03	<10	>10	225	<1	0.06	3	170	8	<5	<20	47	<0.01	<10	4	<10	<1
50	S07-06153	0.2	8.02	20	770	<5	3.15	<1	21	70	108	5.03	1.21	<10	1.84	945	<1	3.16	24	840	36	<5	<20	375	0.24	<10	211	<10	6
51	S07-06154	0.4	8.25	20	730	<5	3.22	<1	18	88	94	4.42	1.19	10	1.81	891	<1	3.23	23	920	34	<5	<20	396	0.25	<10	200	<10	7
52	S07-06155	0.2	8.69	30	940	<5	3.78	<1	31	144	65	6.75	1.51	10	3.10	1218	<1	1.75	49	1170	38	<5	<20	463	0.24	<10	288	<10	9
53	S07-06156	0.2	7.91	20	735	<5	4.07	<1	27	112	106	6.13	1.21	10	2.34	1128	<1	3.10	37	1190	34	<5	<20	639	0.27	<10	245	<10	8
54	S07-06157	<0.2	7.78	20	1135	<5	4.27	<1	25	123	104	5.83	1.68	10	2.41	1166	<1	2.42	36	1030	38	<5	<20	514	0.26	<10	282	<10	9
55	S07-06158	0.4	8.42	30	1090	<5	4.53	<1	30	120	184	6.60	1.68	10	2.58	1135	<1	2.45	44	1190	40	<5	<20	398	0.29	<10	321	<10	10
56	S07-06159	0.6	8.12	30	685	<5	4.28	<1	31	119	227	6.44	1.43	10	2.33	1059	1	2.70	38	1190	66	<5	<20	387	0.24	<10	273	<10	11
57	S07-06160	0.6	7.41	30	560	<5	4.31	<1	35	304	294	6.32	1.71	10	3.27	1095	<1	1.72	93	1110	48	<5	<20	338	0.19	<10	304	<10	9
58	S07-06161	0.2	7.06	30	430	<5	3.99	<1	35	365	214	6.68	1.78	10	3.71	1065	<1	1.16	120	960	30	<5	<20	312	0.14	<10	306	<10	8
59	S07-06162	0.2	7.63	20	1120	<5	4.21	<1	29	208	114	6.56	1.91	10	3.17	1179	<1	1.78	65	1090	34	<5	<20	323	0.21	<10	281	<10	9
60	S07-06163	0.8	7.43	30	975	<5	3.69	<1	21	156	237	4.97	1.68	20	2.07	885	3	2.22	37	1160	48	<5	<20	377	0.25	<10	274	<10	11
61	S07-06164	0.2	7.20	25	870	<5	3.29	<1	25	126	152	5.57	2.11	10	2.51	1031	<1	1.81	35	1010	34	<5	<20	431	0.23	<10	287	<10	10

QC DATA:


Repeat:

1	S07-06104	<0.2	8.86	25	640	<5	3.31	<1	19	169	72	5.29	1.74	<10	1.67	1139	<1	3.05	18	820	32	<5	<20	410	0.29	<10	186	<10	6
10	S07-06113	<0.2	7.32	15	860	<5	3.10	<1	8	63	43	2.55	2.27	20	0.89	724	<1	1.07	7	500	28	<5	<20	227	0.17	<10	54	<10	9
19	S07-06122	7.44		15	980	<5	3.39	<1	7	81	26	2.56	1.92		0.93	707	<1	1.11	7	510	28	<5	<20	247	0.19	<10		10	10
36	S07-06137	7.71		15	705	<5	3.53	<1	24	100	134	5.87	1.63		1.3	47	<1	2.35	27	710	32	<5	<20	314	0.23	<10	25	10	
45	S07-06138	<0.2	7.67	15	515	<5	3.84	<1	23	107	82	5.33	0.73		2.34	1046	<1	2.92	35	980	32	<5	<20	414	0.29	<10	227	<10	9


Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
Resplit:																														
1	S07-06104	<0.2	8.66	25	600	<5	3.29	<1	19	141	64	4.99	1.54	10	1.53	1115	<1	2.79	16	810	32	<5	<20	421	0.28	<10	180	<10	6	96
36	S07-06139	0.2	7.74	15	745	<5	3.75	<1	25	97	127	5.95	1.81	<10	2.45	1141	<1	2.45	27	710	30	<5	<20	311	0.24	<10	265	<10	5	88
Standard:																														
Stsd3		0.5	5.82	35	1480	<5	2.94	<1	18	66	42	4.39	1.36	40	1.36	2738	7	1.18	34	1740	58	<5	<20	283	0.38	<10	120	<10	34	225
Stsd3		0.4	5.81	25	1390	<5	2.46	<1	17	60	41	4.14	1.39	30	1.27	2537	6	1.11	32	1650	56	<5	<20	258	0.34	<10	115	<10	32	203

ICP: 4 ACID DIGEST/ICP-FINISH
AG: 4 ACID DIGEST/AA-FINISH

JJ/nw
df/d2292s
XLS/07



ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2299

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

24-Mar-08


Attention: Bob Singh

No. of samples received: 133
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-162
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-19618	<0.03	<0.001
2	S07-19619	<0.03	<0.001
3	S07-19620	<0.03	<0.001
4	S07-19621	<0.03	<0.001
5	S07-19622	<0.03	<0.001
6	S07-19623	<0.03	<0.001
7	S07-19624	<0.03	<0.001
8	S07-19625	* <0.03	<0.001
9	S07-19626	<0.03	<0.001
10	S07-19627	<0.03	<0.001
11	S07-19628	<0.03	<0.001
12	S07-19629	<0.03	<0.001
13	S07-19630	<0.03	<0.001
14	S07-19631	<0.03	<0.001
15	S07-19632	<0.03	<0.001
16	S07-19633	<0.03	<0.001
17	S07-19634	<0.03	<0.001
18	S07-19635	<0.03	<0.001
19	S07-19636	* 0.43	0.013
20	S07-19637	<0.03	<0.001
21	S07-19638	<0.03	<0.001
22	S07-19639	<0.03	<0.001
23	S07-19640	<0.03	<0.001
24	S07-19641	<0.03	<0.001
25	S07-19642	<0.03	<0.001
26	S07-19643	<0.03	<0.001
27	S07-19644	<0.03	<0.001
28	S07-19645	<0.03	<0.001

* = 30g FA


ECOTECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	S07-19646	<0.03	<0.001
30	S07-19647	<0.03	<0.001
31	S07-19648	<0.03	<0.001
32	S07-19649	<0.03	<0.001
33	S07-19650	<0.03	<0.001
34	S07-19651	<0.03	<0.001
35	S07-19652	<0.03	<0.001
36	S07-19653	0.05	0.001
37	S07-19654	<0.03	<0.001
38	S07-19655	<0.03	<0.001
39	S07-19656	<0.03	<0.001
40	S07-19657	<0.03	<0.001
41	S07-19658	<0.03	<0.001
42	S07-19659	<0.03	<0.001
43	S07-19660	<0.03	<0.001
44	S07-19661	<0.03	<0.001
45	S07-19662	<0.03	<0.001
46	S07-19663	<0.03	<0.001
47	S07-19664	<0.03	<0.001
48	S07-19665	<0.03	<0.001
49	S07-19666	<0.03	<0.001
50	S07-19667	<0.03	<0.001
51	S07-19668	<0.03	<0.001
52	S07-19669	<0.03	<0.001
53	S07-19670	<0.03	<0.001
54	S07-19671	6.58	0.192
55	S07-19672	<0.03	<0.001
56	S07-19673	0.04	0.001
57	S07-19674	<0.03	<0.001
58	S07-19675	0.04	0.001
59	S07-19676	<0.03	<0.001
60	S07-19677	<0.03	<0.001
61	S07-19678	<0.03	<0.001
62	S07-19679	<0.03	<0.001
63	S07-19680	<0.03	<0.001
64	S07-19681	<0.03	<0.001
65	S07-19682	<0.03	<0.001
66	S07-19683	<0.03	<0.001
67	S07-19684	<0.03	<0.001
68	S07-19685	<0.03	<0.001
69	S07-19686	<0.03	<0.001
70	S07-19687	<0.03	<0.001
71	S07-19688	<0.03	<0.001
72	S07-19689	<0.03	<0.001

= 30g FA




 ECO TECH LABORATORY LTD.

 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
73	S07-19690	<0.03	<0.001
74	S07-19691	<0.03	<0.001
75	S07-19692	<0.03	<0.001
76	S07-19693	<0.03	<0.001
77	S07-19694	<0.03	<0.001
78	S07-19695	0.06	0.002
79	S07-19696	* <0.03	<0.001
80	S07-19697	<0.03	<0.001
81	S07-19698	<0.03	<0.001
82	S07-19699	<0.03	<0.001
83	S07-19700	<0.03	<0.001
84	S07-19701	<0.03	<0.001
85	S07-19702	<0.03	<0.001
86	S07-19703	<0.03	<0.001
87	S07-19704	<0.03	<0.001
88	S07-19705	0.06	0.002
89	S07-19706	* 2.09	0.061
90	S07-19707	0.08	0.002
91	S07-19708	0.07	0.002
92	S07-19709	0.07	0.002
93	S07-19710	0.03	0.001
94	S07-19711	<0.03	<0.001
95	S07-19712	<0.03	<0.001
96	S07-19713	<0.03	<0.001
97	S07-19714	<0.03	<0.001
98	S07-19715	<0.03	<0.001
99	S07-19716	<0.03	<0.001
100	S07-19717	<0.03	<0.001
101	S07-19718	<0.03	<0.001
102	S07-19719	0.04	0.001
103	S07-19720	<0.03	<0.001
104	S07-19721	0.04	0.001
105	S07-19722	<0.03	<0.001
106	S07-19723	0.13	0.004
107	S07-19724	<0.03	<0.001
108	S07-19725	<0.03	<0.001
109	S07-19726	<0.03	<0.001
110	S07-19727	<0.03	<0.001
111	S07-19728	0.04	0.001
112	S07-19729	0.12	0.003
113	S07-19730	* 0.41	0.012
114	S07-19731	0.04	0.001
115	S07-19732	0.06	0.002
116	S07-19733	0.09	0.002
117	S07-19734	0.05	0.001

* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
118	S07-19735	<0.03	<0.001
119	S07-19736	0.04	0.001
120	S07-19737	0.06	0.002
121	S07-19738	<0.03	<0.001
122	S07-19739	<0.03	<0.001
123	S07-19740	<0.03	<0.001
124	S07-19741	<0.03	<0.001
125	S07-19742	<0.03	<0.001
126	S07-19743	<0.03	<0.001
127	S07-19744	<0.03	<0.001
128	S07-19745	<0.03	<0.001
129	S07-19746	<0.03	<0.001
130	S07-19747	0.06	0.002
131	S07-19748	0.05	0.001
132	S07-19749	0.24	0.007
133	S07-19750	0.17	0.005

QC DATA:**Resplit:**

1	S07-19618	<0.03	<0.001
36	S07-19653	0.05	0.001
71	S07-19688	<0.03	<0.001
106	S07-19723	0.08	0.002

Standard:

OXI54	1.90	0.055
OXI54	1.90	0.055
OXI54	1.90	0.055
OXI54	1.88	0.055
OXI54	1.86	0.054
OXI54	1.88	0.055
OXI54	1.90	0.055
OXI54	1.92	0.056
OXI54	1.88	0.055

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw

XLS/07



 ECO TECH LABORATORY LTD.

Jutta Jealous

B.C. Certified Assayer

CO TECH LABORATORY LTD.
1041 Dallas Drive
AMLOOPS, B.C.
2C 6T4

ICP CERTIFICATE OF ANALYSIS - AK 2007-2299

Skygold Ventures
615 - 800 W. Pender Street
Vancouver, BC
V6B 2V6

none: 250-573-5700
fax : 250-573-4557

No. of samples received: 133
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-162
Samples submitted by: Tasha Gainer

values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al	As	Ba	Bi	Ca	Cd	Co	Cr	Cu	Fe	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	Sb	Sn	Sr	Ti	U	V	W	Y	Zn
1	S07-19618	<0.2	5.33	15	750	<5	2.00	<1	20	261	32	2.72	2.08	20	1.68	1353	14	0.39	119	380	40	<5	<20	118	0.08	<10	96	<10	7	94
2	S07-19619	<0.2	4.93	25	405	<5	4.29	<1	39	502	40	3.96	1.31	<10	5.56	1898	6	0.64	412	570	34	<5	<20	208	0.07	<10	128	<10	7	80
3	S07-19620	<0.2	4.44	20	370	<5	4.72	<1	48	617	60	3.89	1.13	<10	5.92	2134	3	0.54	585	500	42	5	<20	197	0.06	<10	122	<10	7	74
4	S07-19621	<0.2	5.58	15	705	<5	2.37	<1	36	638	60	3.46	1.94	<10	4.28	1839	5	0.61	273	480	28	5	<20	120	0.07	<10	79	<10	8	100
5	S07-19622	<0.2	5.81	<5	1255	<5	2.06	<1	7	50	73	1.85	2.36	10	1.64	898	<1	0.30	20	380	22	<5	<20	89	0.10	<10	41	<10	7	31
6	S07-19623	<0.2	5.32	10	365	<5	1.76	<1	35	609	45	4.59	1.45	<10	5.84	1237	<1	0.60	196	760	20	<5	<20	94	0.10	<10	125	<10	7	61
7	S07-19624	<0.2	4.85	30	375	<5	3.23	<1	26	512	7	2.87	1.44	10	4.85	1381	<1	0.44	249	420	18	5	<20	129	0.10	<10	68	<10	9	42
8	S07-19625	<0.2	7.28	<5	485	<5	2.85	<1	11	46	36	3.99	1.01	10	1.33	805	3	2.32	28	810	26	<5	<20	277	0.36	<10	103	<10	18	49
9	S07-19626	<0.2	4.42	25	310	<5	3.06	<1	27	805	15	2.90	1.27	10	4.78	1277	<1	0.43	258	420	18	10	<20	120	0.10	<10	68	<10	8	46
10	S07-19627	0.3	4.10	10	300	<5	2.57	<1	23	476	35	2.72	1.00	<10	4.89	1004	<1	0.35	169	390	16	<5	<20	127	0.07	<10	71	<10	7	40
11	S07-19628	<0.2	5.07	5	645	<5	1.51	<1	15	327	30	2.37	1.92	20	3.34	1132	<1	0.75	98	430	22	<5	<20	120	0.08	<10	54	<10	8	54
12	S07-19629	<0.2	5.03	5	800	<5	1.75	<1	8	187	39	1.98	1.83	20	1.11	1097	6	0.96	21	550	24	<5	<20	93	0.11	<10	31	<10	7	30
13	S07-19630	<0.2	6.12	<5	1190	<5	0.92	<1	5	68	23	1.70	2.59	20	1.00	723	<1	0.70	14	320	28	<5	<20	54	0.11	<10	31	<10	8	41
14	S07-19631	<0.2	5.60	<5	1165	<5	0.94	<1	7	131	12	1.68	2.53	30	1.95	781	<1	0.60	33	300	22	<5	<20	75	0.11	<10	30	<10	8	46
15	S07-19632	<0.2	5.40	<5	1080	<5	0.68	<1	6	104	47	1.83	2.34	20	1.66	708	<1	0.73	21	270	24	<5	<20	65	0.09	<10	26	<10	7	37
16	S07-19633	<0.2	5.52	<5	970	<5	1.22	<1	8	295	16	2.24	2.06	20	1.50	977	<1	0.89	42	320	26	<5	<20	76	0.10	<10	45	<10	7	42
17	S07-19634	<0.2	5.46	<5	750	<5	1.09	<1	8	115	60	2.21	1.63	20	1.34	814	<1	1.73	20	400	30	<5	<20	83	0.11	<10	37	<10	6	35
18	S07-19635	<0.2	4.85	<5	505	<5	1.09	<1	8	227	45	2.13	1.14	20	1.73	604	<1	1.65	23	370	26	<5	<20	78	0.09	<10	35	<10	6	33
19	S07-19636	0.8	4.82	85	365	<5	0.26	<1	8	25	30	3.11	4.52	10	0.29	165	3	0.16	14	490	20	35	<20	52	0.34	<10	75	<10	11	49
20	S07-19637	0.6	5.04	15	380	<5	4.37	<1	32	540	15	3.88	1.00	10	5.14	2072	<1	0.60	244	600	28	<5	<20	230	0.06	<10	100	<10	8	71
21	S07-19638	<0.2	5.24	35	310	<5	5.47	<1	43	716	39	4.83	0.92	<10	6.06	2496	<1	0.40	287	710	24	5	<20	273	0.05	<10	111	<10	8	83
22	S07-19639	<0.2	5.80	<5	910	<5	1.17	<1	10	151	15	2.07	1.96	20	2.42	680	<1	0.88	54	330	24	<5	<20	73	0.09	<10	40	<10	10	38
23	S07-19640	0.2	4.97	<5	290	<5	2.49	<1	24	470	47	3.42	0.66	10	3.56	1519	<1	1.40	142	560	30	<5	<20	144	0.09	<10	82	<10	7	62
24	S07-19641	<0.2	6.11	10	455	<5	1.97	<1	16	249	76	2.86	1.02	10	2.98	1331	<1	1.83	98	380	28	<5	<20	130	0.11	<10	48	<10	11	52
25	S07-19642	<0.2	5.89	<5	810	<5	1.91	<1	17	223	12	2.57	1.73	10	3.24	1847	<1	0.96	126	520	24	<5	<20	106	0.12	<10	59	<10	11	63

Et #.	Tag	Ag	Al	As	Ba	Bi	Ca	Cd	Co	Cr	Cu	Fe	K	Mg	Mn	Mo	Na	Ni	P	Pb	Sb	Sn	Sr	Ti	U	V	Y	Zn		
26	S07-19643	<0.2	5.40	<5	1085	<5	0.60	<1	3	73	39	1.69	2.07	10	1.31	880	<1	1.34	7	320	22	<5	<20	68	0.13	<10	28	<10	6	26
27	S07-19644	<0.2	5.89	<5	990	<5	1.23	<1	12	157	37	2.43	2.06	10	2.98	1777	<1	0.75	65	390	24	<5	<20	84	0.12	<10	43	<10	10	63
28	S07-19645	<0.2	5.11	<5	780	<5	1.28	<1	12	300	27	2.44	1.68	10	2.00	1364	<1	0.79	64	310	32	<5	<20	94	0.11	<10	34	<10	6	57
29	S07-19646	<0.2	5.73	<5	820	<5	1.11	<1	11	122	48	2.39	1.72	20	1.93	1064	<1	1.26	51	330	30	<5	<20	103	0.12	<10	32	<10	6	51
30	S07-19647	<0.2	5.21	<5	720	<5	2.02	<1	17	252	81	2.53	1.58	10	3.05	1372	<1	0.65	108	380	28	<5	<20	138	0.11	<10	50	<10	9	55
31	S07-19648	<0.2	5.27	<5	1145	<5	0.82	<1	10	123	8	2.24	2.11	20	2.09	1263	<1	0.45	47	370	22	<5	<20	73	0.11	<10	36	<10	7	50
32	S07-19649	<0.2	4.38	<5	855	<5	0.89	<1	11	121	51	2.35	1.49	20	1.22	2011	<1	0.81	31	270	30	<5	<20	67	0.12	<10	62	<10	5	61
33	S07-19650	<0.2	0.08	<5	5	<5	>10	<1	<1	4	<1	0.56	0.02	<10	>10	205	<1	0.02	2	140	<2	<5	<20	46	<0.01	<10	2	<10	<1	12
34	S07-19651	<0.2	4.82	<5	1255	<5	0.72	<1	7	140	26	2.09	2.04	10	1.35	1964	<1	0.44	19	180	22	<5	<20	51	0.14	<10	54	<10	7	70
35	S07-19652	<0.2	5.19	10	745	<5	0.95	<1	16	188	92	3.09	1.41	20	1.39	2545	<1	1.74	45	410	34	<5	<20	89	0.14	<10	58	<10	8	95
36	S07-19653	1.5	4.37	10	445	<5	1.08	<1	17	237	78	2.49	1.05	20	1.72	1380	<1	1.24	58	430	250	<5	<20	112	0.10	<10	50	<10	5	54
37	S07-19654	<0.2	4.27	10	155	<5	2.99	<1	29	440	104	3.48	0.59	<10	5.17	1537	<1	0.86	188	560	20	<5	<20	181	0.08	<10	95	<10	6	47
38	S07-19655	<0.2	5.20	5	370	<5	2.26	<1	22	443	51	3.24	1.00	10	3.61	1395	<1	1.00	147	570	30	<5	<20	171	0.10	<10	93	<10	7	59
39	S07-19656	<0.2	5.41	10	945	<5	1.30	<1	7	231	69	2.19	1.92	20	1.36	1045	4	0.64	24	300	42	<5	<20	105	0.11	<10	47	<10	7	41
40	S07-19657	<0.2	5.36	<5	1230	<5	1.20	<1	6	89	25	1.51	2.33	20	1.11	773	<1	0.49	12	290	24	<5	<20	68	0.11	<10	28	<10	8	28
41	S07-19658	<0.2	5.64	<5	1500	<5	1.02	<1	4	177	24	1.64	2.76	20	1.29	465	<1	0.21	13	260	20	<5	<20	53	0.11	<10	24	<10	7	19
42	S07-19659	<0.2	4.72	20	340	<5	3.58	<1	32	737	19	3.66	0.85	10	6.47	1250	<1	0.32	305	520	20	5	<20	141	0.08	<10	88	<10	7	66
43	S07-19660	<0.2	4.52	10	70	<5	3.77	<1	49	945	85	4.70	0.31	<10	8.31	1336	<1	0.31	465	580	22	10	<20	150	0.06	<10	114	<10	6	66
44	S07-19661	<0.2	4.98	15	115	<5	3.57	<1	45	911	40	4.46	0.46	<10	8.07	1301	<1	0.37	400	590	20	10	<20	136	0.06	<10	109	<10	6	63
45	S07-19662	<0.2	2.98	10	30	<5	5.65	<1	43	941	34	4.15	0.14	<10	7.74	1644	<1	0.17	444	500	16	10	<20	216	0.03	<10	88	<10	5	47
46	S07-19663	<0.2	5.68	5	475	<5	2.65	<1	28	458	34	3.30	1.17	<10	6.10	1061	<1	0.32	273	520	20	<5	<20	91	0.10	<10	70	<10	8	55
47	S07-19664	<0.2	6.38	<5	640	<5	0.75	<1	16	300	187	2.99	2.27	10	2.37	586	<1	0.28	62	530	22	<5	<20	42	0.15	<10	34	<10	9	32
48	S07-19665	<0.2	1.51	<5	155	<5	3.36	<1	7	175	10	1.86	0.48	<10	1.95	1127	<1	0.07	34	140	6	<5	<20	100	0.03	<10	23	<10	3	18
49	S07-19666	<0.2	2.87	5	155	<5	4.32	<1	24	371	32	2.98	0.59	<10	3.83	1829	<1	0.18	159	480	12	<5	<20	125	0.05	<10	75	<10	4	50
50	S07-19667	<0.2	6.19	<5	935	<5	3.52	<1	21	359	36	3.06	2.11	<10	4.01	1625	<1	0.47	97	530	24	<5	<20	123	0.14	<10	85	<10	8	55
51	S07-19668	<0.2	5.69	10	745	<5	1.68	<1	27	483	98	4.30	1.84	<10	4.37	1362	<1	0.72	141	650	24	<5	<20	115	0.15	<10	133	<10	6	61
52	S07-19669	<0.2	4.31	20	270	<5	4.23	<1	36	858	97	4.71	1.11	<10	5.87	2129	<1	0.78	267	580	24	10	<20	212	0.07	<10	120	<10	6	63
53	S07-19670	<0.2	4.69	15	315	<5	3.88	<1	42	915	62	4.58	1.18	<10	6.05	1752	3	0.90	300	590	26	10	<20	210	0.09	<10	118	<10	7	88
54	S07-19671	6.2	3.82	130	285	<5	0.38	<1	8	48	61	3.10	2.93	<10	0.27	229	6	0.54	21	420	24	65	<20	94	0.31	<10	52	<10	10	58
55	S07-19672	<0.2	5.39	<5	440	<5	2.34	<1	13	140	65	2.29	2.48	20	1.91	756	2	0.34	37	330	28	<5	<20	113	0.14	<10	56	<10	8	22
56	S07-19673	<0.2	5.55	5	1045	<5	1.51	<1	18	350	65	2.43	2.12	20	2.45	673	3	0.40	77	340	26	<5	<20	100	0.13	<10	105	<10	8	46
57	S07-19674	<0.2	5.71	5	1270	<5	3.40	<1	16	140	49	2.16	2.38	20	2.20	939	30	0.34	43	1040	28	<5	<20	171	0.12	<10	103	<10	15	32
58	S07-19675	0.2	4.10	25	205	<5	3.82	<1	32	762	81	4.66	1.55	10	3.80	1363	8	0.45	230	530	28	5	<20	210	0.06	<10	187	<10	6	61
59	S07-19676	<0.2	4.42	20	305	<5	3.08	<1	24	512	131	5.01	1.80	10	3.76	1342	20	0.44	197	690	28	5	<20	145	0.07	<10	219	<10	5	69
60	S07-19677	<0.2	4.79	30	570	<5	4.36	<1	27	456	101	3.82	2.00	10	3.81	1541	20	0.47	154	560	28	<5	<20	220	0.08	<10	191	<10	7	95
61	S07-19678	<0.2	4.94	25	985	<5	4.47	<1	23	639	78	3.47	2.11	10	3.44	1890	9	0.53	159	480	30	5	<20	202	0.07	<10	122	<10	8	71
62	S07-19679	<0.2	6.09	15	1105	<5	3.11	<1	29	381	94	4.78	2.17	<10	4.66	1892	1	0.84	117	910	26	<5	<20	161	0.13	<10	190	<10	5	79
63	S07-19680	<0.2	5.23	10	680	<5	1.79	<1	34	677	52	4.33	1.33	10	5.02	1303	6	0.74	212	790	26	5	<20	128	0.09	<10	164	<10	5	87
64	S07-19681	<0.2	4.02	15	65	<5	7.22	<1	54	1069	48	5.22	0.27	<10	8.10	3231	<1	0.34	478	490	36	10	<20	228	0.04	<10	138	<10	7	100
65	S07-19682	<0.2	4.93	5	460	<5	4.96	<1	32	406	6	4.27	0.91	<10	6.07	2578	<1	0.45	246	600	26	<5	<20	203	0.07	<10	121	<10	7	94

Et #.	Tag	Ag	Al	As	Ba	Bi	Ca	Cd	Co	Cr	Cu	Fe	K	Mg	Mn	Mo	Na	Ni	P	Pb	Sb	Sn	Sr	Ti	U	V	Y	Zn		
66	S07-19683	<0.2	5.18	15	505	<5	3.33	<1	41	627	7	4.96	0.96	10	5.15	2625	<1	0.36	293	700	32	5	<20	143	0.09	<10	132	<10	6	123
67	S07-19684	0.2	4.15	<5	635	<5	1.91	<1	21	240	175	3.19	1.05	20	2.16	2392	<1	0.46	77	380	38	<5	<20	118	0.14	<10	128	<10	6	85
68	S07-19685	<0.2	8.16	<5	2795	<5	0.99	<1	12	89	220	2.06	3.40	20	1.67	2432	<1	0.67	26	520	36	<5	<20	88	0.19	<10	127	<10	9	83
69	S07-19686	<0.2	8.15	5	2710	<5	0.98	<1	13	105	214	2.21	3.40	20	1.73	2455	<1	0.58	31	540	36	<5	<20	84	0.21	<10	144	<10	9	85
70	S07-19687	0.2	7.25	<5	2195	<5	1.13	<1	15	58	299	2.30	2.73	20	1.80	3145	<1	1.39	30	510	38	<5	<20	103	0.20	<10	136	<10	9	102
71	S07-19688	0.2	4.43	5	505	<5	1.60	<1	26	371	81	3.92	0.80	20	2.80	2420	<1	0.80	127	500	34	<5	<20	105	0.14	<10	132	<10	5	90
72	S07-19689	<0.2	5.13	<5	1435	<5	0.75	<1	8	89	61	2.24	1.70	20	1.41	2451	<1	0.83	23	350	26	<5	<20	76	0.13	<10	78	<10	6	62
73	S07-19690	<0.2	6.00	<5	1485	<5	0.69	<1	5	182	18	2.07	1.68	20	1.21	2434	<1	1.85	15	420	28	<5	<20	115	0.13	<10	36	<10	6	69
74	S07-19691	<0.2	6.18	10	1600	<5	0.93	<1	19	122	166	2.99	1.95	20	1.85	2257	<1	1.16	54	430	38	<5	<20	113	0.16	<10	58	<10	6	79
75	S07-19692	<0.2	4.38	20	230	<5	5.30	<1	52	700	37	4.94	0.44	<10	7.64	2269	<1	0.45	450	570	28	5	<20	391	0.05	<10	117	<10	6	66
76	S07-19693	0.2	3.71	35	75	<5	6.69	<1	57	795	2	5.09	0.34	<10	9.58	2480	<1	0.38	521	510	18	10	<20	556	0.02	<10	121	<10	6	67
77	S07-19694	0.2	4.73	10	560	<5	1.96	<1	31	305	56	4.08	0.94	10	3.87	1822	<1	1.00	144	540	28	<5	<20	183	0.12	<10	96	<10	6	75
78	S07-19695	<0.2	5.67	<5	1390	<5	1.50	<1	16	90	59	2.45	1.74	20	1.55	2856	<1	1.66	40	410	30	<5	<20	157	0.15	<10	82	<10	6	96
79	S07-19696	<0.2	0.08	<5	20	<5	>10	<1	1	3	1	0.56	0.03	<10	>10	217	<1	0.02	3	180	<2	<5	<20	51	<0.01	<10	3	<10	<1	12
80	S07-19697	<0.2	5.46	15	1190	<5	0.78	<1	10	93	31	2.22	1.84	10	1.67	1826	<1	1.76	43	340	26	<5	<20	119	0.13	<10	35	<10	5	61
81	S07-19698	0.4	4.90	35	830	<5	2.19	<1	22	227	91	2.83	1.77	20	2.82	2305	<1	0.93	132	590	32	<5	<20	205	0.12	<10	92	<10	7	82
82	S07-19699	<0.2	5.37	15	840	<5	1.56	<1	13	191	39	2.32	1.74	10	2.33	1658	<1	0.90	77	360	28	<5	<20	159	0.12	<10	52	<10	6	50
83	S07-19700	0.2	5.57	<5	920	<5	1.08	<1	7	104	95	2.01	1.59	10	1.53	1265	<1	1.51	45	380	24	<5	<20	131	0.14	<10	42	<10	5	45
84	S07-19701	0.4	4.79	<5	1215	<5	1.52	<1	8	92	46	1.98	1.50	20	1.48	1633	<1	0.84	23	260	28	<5	<20	136	0.13	<10	104	<10	6	35
85	S07-19702	0.6	4.44	15	680	<5	3.64	<1	26	341	35	3.00	1.11	10	4.90	2436	<1	0.80	239	530	22	<5	<20	262	0.08	<10	103	<10	6	62
86	S07-19703	<0.2	5.32	15	1435	<5	1.58	<1	11	134	31	2.16	1.73	10	2.02	1781	<1	0.95	89	290	24	<5	<20	127	0.13	<10	39	<10	5	69
87	S07-19704	<0.2	6.32	5	1685	<5	1.00	<1	13	89	48	2.32	2.09	20	1.70	2321	<1	1.26	28	380	26	<5	<20	126	0.18	<10	85	<10	6	85
88	S07-19705	0.4	5.53	10	840	<5	0.87	<1	28	116	95	4.20	1.27	20	1.63	2315	<1	1.61	67	480	34	<5	<20	122	0.18	<10	97	<10	5	92
89	S07-19706	4.5	4.84	110	215	<5	0.43	1	12	37	595	4.93	2.49	10	1.85	413	7	0.21	26	450	94	50	<20	66	0.30	<10	57	<10	11	682
90	S07-19707	0.2	5.34	35	650	<5	3.67	<1	37	408	10	4.81	1.24	10	5.13	2560	<1	1.03	229	670	44	<5	<20	272	0.11	<10	122	<10	6	122
91	S07-19708	<0.2	5.20	25	910	<5	2.65	<1	30	223	48	4.34	1.52	10	3.51	1904	<1	0.81	84	790	24	<5	<20	197	0.15	<10	161	<10	6	61
92	S07-19709	0.8	5.01	10	1045	<5	1.33	<1	25	198	96	3.57	1.46	20	1.60	2348	<1	0.89	70	550	30	<5	<20	136	0.15	<10	96	<10	5	78
93	S07-19710	0.4	5.51	5	580	<5	0.87	<1	27	174	102	4.30	1.27	20	1.40	2499	<1	1.56	67	560	42	<5	<20	117	0.16	<10	97	<10	6	83
94	S07-19711	0.2	5.59	5	1660	<5	1.18	<1	12	149	68	2.27	2.01	10	1.59	2265	<1	1.18	32	450	28	<5	<20	124	0.16	<10	96	<10	6	70
95	S07-19712	0.2	5.29	<5	1375	<5	1.10	<1	5	134	34	1.77	1.64	10	1.12	2764	<1	1.64	14	310	28	<5	<20	121	0.15	<10	69	<10	5	67
96	S07-19713	<0.2	6.26	<5	1395	<5	0.69	<1	8	62	29	2.19	1.84	20	1.38	2180	<1	1.75	19	290	24	<5	<20	102	0.15	<10	26	<10	6	83
97	S07-19714	<0.2	4.91	5	495	<5	1.45	<1	19	226	97	3.32	0.86	20	1.31	1906	<1	1.39	54	420	42	<5	<20	154	0.14	<10	50	<10	6	80
98	S07-19715	<0.2	4.05	25	230	<5	3.20	<1	32	412	29	3.47	0.65	<10	5.77	1752	<1	0.99	261	580	16	5	<20	228	0.07	<10	82	<10	6	53
99	S07-19716	0.2	4.67	20	260	<5	3.86	<1	39	592	117	3.81	0.75	<10	5.96	1537	<1	1.13	303	530	20	5	<20	275	0.08	<10	82	<10	6	62
100	S07-19717	<0.2	4.93	15	390	<5	2.96	<1	23	279	79	3.25	0.90	10	4.18	1443	<1	1.09	149	530	24	<5	<20	195	0.12	<10	72	<10	6	42
101	S07-19718	<0.2	4.16	20	220	<5	3.95	<1	31	481	36	4.37	0.77	<10	5.45	1790	<1	0.91	247	590	18	<5	<20	199	0.10	<10	106	<10	6	60
102	S07-19719	<0.2	4.55	20	255	<5	4.25	<1	35	490	68	4.34	0.86	<10	5.81	1841	<1	1.05	252	590	20	<5	<20	218	0.10	<10	111	<10	6	56
103	S07-19720	<0.2	5.51	25	435	<5	3.62	<1	45	561	69	5.08	1.26	<10	6.14	2165	<1	1.07	259	800	22	5	<20	176	0.14	<10	185	<10	6	64
104	S07-19721	0.4	5.90	20	865	<5	2.84	<1	23	165	102	3.78	2.32	20	1.87	2594	<1	0.55	70	480	28	<5	<20	155	0.18	<10	186	<10	5	61
105	S07-19722	<0.2	5.27	15	795	<5	1.85	<1	15	163	54	2.30	2.39	10	1.65	1167	2	0.29	46	400	22	<5	<20	102	0.15	<10	82	<10	6	33

Et #.	Tag	Ag	Al	As	Ba	Bi	Ca	Cd	Co	Cr	Cu	Fe	K	Mg	Mn	Mo	Na	Ni	P	Pb	Sb	Sn	Sr	Ti	U	V	Y	Zn		
106	S07-19723	0.2	4.41	10	120	<5	2.23	<1	17	196	71	2.75	2.21	20	1.54	916	15	0.15	51	580	28	<5	<20	94	0.09	<10	150	<10	7	75
107	S07-19724	0.2	3.35	10	255	<5	2.25	<1	14	209	59	2.28	1.43	10	1.76	1062	<1	0.17	51	360	24	<5	<20	97	0.07	<10	58	<10	4	44
108	S07-19725	<0.2	4.51	25	245	<5	2.46	<1	34	379	115	4.11	1.41	10	3.78	1372	<1	0.52	197	610	28	<5	<20	143	0.08	<10	100	<10	5	71
109	S07-19726	0.2	4.53	25	180	<5	4.82	<1	52	836	56	5.07	0.98	<10	7.94	1972	<1	1.00	406	600	36	10	<20	243	0.03	<10	125	<10	3	100
110	S07-19727	0.2	4.55	20	145	<5	4.24	1	27	426	115	5.05	1.63	10	3.36	1258	23	0.34	153	940	26	5	<20	209	0.07	<10	185	<10	6	112
111	S07-19728	0.8	4.84	30	105	<5	4.44	3	27	340	55	5.62	1.92	20	2.68	1018	34	0.25	173	1000	36	<5	<20	196	0.08	<10	203	<10	7	167
112	S07-19729	1.4	4.81	10	80	<5	2.24	3	17	226	88	4.97	2.23	10	1.35	525	43	0.18	79	680	50	10	<20	104	0.09	<10	214	<10	6	191
113	S07-19730	0.8	4.72	125	205	<5	0.27	<1	9	24	29	2.79	3.95	10	0.30	187	3	0.19	17	450	20	40	<20	56	0.41	<10	76	<10	10	54
114	S07-19731	0.4	4.56	45	145	<5	3.71	3	35	588	51	5.32	1.74	10	4.91	1115	29	0.42	288	600	30	10	<20	214	0.07	<10	176	<10	6	233
115	S07-19732	0.6	4.90	40	120	<5	3.38	2	25	286	56	5.05	1.94	20	2.47	797	37	0.23	148	1230	32	5	<20	163	0.10	<10	222	<10	8	164
116	S07-19733	1.4	5.10	35	125	<5	3.35	2	22	225	71	5.52	2.09	20	2.43	762	36	0.31	127	820	48	10	<20	168	0.09	<10	224	<10	8	172
117	S07-19734	1.0	4.91	15	60	<5	2.13	3	19	285	70	5.07	2.25	10	1.25	482	41	0.19	87	860	32	5	<20	105	0.09	<10	240	<10	7	175
118	S07-19735	0.4	4.29	30	115	<5	3.43	2	20	388	144	5.32	1.82	10	2.34	1043	37	0.15	138	860	28	<5	<20	155	0.07	<10	226	<10	6	129
119	S07-19736	0.2	5.76	15	355	<5	3.90	<1	22	239	105	3.29	2.64	10	3.01	1487	4	0.33	75	480	30	<5	<20	187	0.11	<10	134	<10	7	61
120	S07-19737	<0.2	5.75	25	235	<5	1.42	<1	22	184	80	4.34	2.51	20	2.10	1172	<1	0.47	82	500	26	<5	<20	85	0.13	<10	127	<10	4	64
121	S07-19738	<0.2	5.38	15	510	<5	3.69	<1	19	310	50	3.37	2.02	10	2.70	2308	12	0.75	106	660	26	5	<20	180	0.09	<10	94	<10	5	78
122	S07-19739	<0.2	5.29	35	350	<5	2.86	<1	27	426	27	3.43	1.78	10	4.72	1536	<1	1.01	166	500	22	<5	<20	182	0.07	<10	93	<10	5	84
123	S07-19740	<0.2	4.88	65	125	5	4.09	<1	51	986	34	4.68	1.26	<10	7.46	1716	<1	0.98	404	590	30	10	<20	221	0.04	<10	115	<10	4	98
124	S07-19741	<0.2	3.85	25	30	<5	5.81	<1	39	780	62	5.08	0.58	<10	7.94	1760	5	0.93	276	550	22	10	<20	289	0.03	<10	121	<10	5	72
125	S07-19742	<0.2	0.06	<5	15	<5	>10	<1	<1	2	<1	0.58	0.02	<10	>10	209	<1	0.02	3	160	<2	<5	<20	45	<0.01	<10	2	<10	<1	12
126	S07-19743	<0.2	4.46	55	180	<5	5.38	<1	41	828	60	5.06	1.14	<10	6.45	1663	4	0.74	329	760	26	10	<20	262	0.04	<10	137	<10	5	99
127	S07-19744	<0.2	4.81	20	445	<5	3.78	<1	19	254	42	2.75	1.86	20	3.08	1177	<1	0.57	90	410	20	<5	<20	198	0.09	<10	73	<10	8	35
128	S07-19745	0.4	4.07	80	130	<5	6.83	<1	67	1588	62	5.39	1.22	<10	8.33	2125	<1	0.67	744	560	86	20	<20	381	0.02	<10	113	<10	4	158
129	S07-19746	0.2	4.72	55	270	<5	4.97	<1	40	919	38	4.91	1.81	<10	4.90	1638	8	0.37	307	880	34	10	<20	275	0.05	<10	146	<10	5	148
130	S07-19747	0.2	4.91	25	130	<5	3.72	2	19	292	87	5.03	2.17	20	1.78	796	30	0.14	92	1040	28	10	<20	154	0.09	<10	255	<10	6	209
131	S07-19748	0.4	3.72	60	185	<5	3.99	<1	31	856	62	4.19	1.94	10	4.03	1265	10	0.26	292	680	20	10	<20	238	0.04	<10	181	<10	5	113
132	S07-19749	2.2	5.16	20	90	<5	3.39	1	19	207	69	4.64	2.37	20	1.60	930	32	0.16	76	1140	56	10	<20	176	0.09	<10	267	<10	7	133
133	S07-19750	1.8	5.33	30	125	<5	4.81	3	25	349	71	5.08	2.29	20	2.38	1374	30	0.20	116	1030	56	10	<20	240	0.09	<10	242	<10	8	237

IC DATA:


repeat:


1	S07-19618	<0.2	5.56	20	775	<5	2.14	<1	21	254	33	2.82	2.15	20	1.72	1417	15	0.40	122	410	42	<5	<20	124	0.08	<10	96	<10	7	98
10	S07-19627	0.4	4.22	10	300	<5	2.63	<1	23	480	35	2.75	1.00	<10	4.88	1023	<1	0.35	171	400	18	5	<20	128	0.07	<10	73	<10	7	39
19	S07-19636	0.6	4.06	100	380	<5	0.27	<1	8	26	31	3.12	4.49	10	0.30	160	3	0.17	15	530	21	40	<20	54	0.39	<10	76	<10	11	50
36	S07-19653	1.4	4.48	15	450	<5	1.11	<1	17	229	81	2.61	1.07	20	1.75	1385	<1	1.27	59	450	236	<5	<20	112	0.11	<10	51	<10	5	53
45	S07-19662	<0.2	2.88	15	30	<5	5.42	<1	40	975	33	3.95	0.15	<10	7.56	1593	<1	0.18	424	490	14	10	<20	212	0.03	<10	89	<10	5	44
54	S07-19671	6.4	3.71	130	270	<5	0.41	<1	7	42	50	2.76	2.83	<10	0.25	237	6	0.57	22	420	25	65	<20	104	0.30	<10	51	<10	10	58
71	S07-19688	<0.2	4.46	<5	520	<5	1.62	<1	27	379	85	4.03	0.80	20	2.89	2435	<1	0.80	128	510	36	<5	<20	109	0.15	<10	136	<10	5	92
80	S07-19697	<0.2	5.49	10	1190	<5	0.80	<1	9	88	30	2.31	1.81	20	1.72	1867	<1	1.74	44	350	24	<5	<20	119	0.14	<10	35	<10	5	66
106	S07-19723	0.2	4.58	10	100	<5	2.36	<1	18	210	70	2.80	2.23	10	1.63	929	15	0.15	54	610	28	<5	<20	101	0.10	<10	152	<10	7	79
115	S07-19732	0.6	4.69	35	115	<5	3.33	2	25	298	57	4.95	1.93	20	2.33	731	35	0.24	144	1160	32	5	<20	156	0.10	<10	225	<10	8	156
124	S07-19741	0.2	3.71	20	30	<5	5.55	<1	39	784	65	4.68	0.58	<10	7.97	1753	5	0.90	274	540	24	10	<20	293	0.02	<10	121	<10	5	72

Et #.	Tag #	Ag	Al	As	Ba	Bi	Ca	Cd	Co	Cr	Cu	Fe	K	Mg	Mn	Mo	Na	Ni	P	Pb	Sb	Sn	Sr	Ti	U	V	W	Y	Zn	
Replits:																														
1	S07-19618	<0.2	5.53	20	810	<5	1.93	<1	17	266	34	2.51	2.26	20	1.59	1330	13	0.38	113	380	40	<5	<20	116	0.09	<10	94	<10	8	90
36	S07-19653	1.2	4.46	15	510	<5	1.11	<1	19	253	93	2.55	1.21	20	1.82	1508	<1	1.26	66	470	228	<5	<20	118	0.11	<10	56	<10	7	61
71	S07-19688	<0.2	4.55	<5	490	<5	1.55	<1	26	342	77	4.03	0.74	20	2.99	2413	<1	0.80	125	520	34	<5	<20	98	0.15	<10	124	<10	5	94
106	S07-19723	0.2	4.26	10	110	<5	2.36	<1	16	209	68	2.77	2.25	20	1.57	896	18	0.14	55	610	28	<5	<20	96	0.10	<10	157	<10	7	77
Standard:																														
sd3		0.4	5.62	25	1190	<5	2.27	<1	15	59	39	3.87	1.37	30	1.30	2489	5	1.34	31	1790	56	<5	<20	317	0.36	<10	118	<10	27	194
sd3		0.5	5.66	25	1275	<5	2.33	<1	15	61	37	3.86	1.36	40	1.36	2546	5	1.44	33	1880	60	<5	<20	327	0.33	<10	114	<10	29	207
sd3		0.5	5.79	25	1255	<5	2.37	<1	16	60	38	3.83	1.32	30	1.38	2598	5	1.41	33	1800	58	<5	<20	332	0.34	<10	110	<10	29	198
sd3		0.4	5.72	23	1300	<5	2.38	<1	16	62	38	3.89	1.40	30	1.40	2594	5	1.49	35	1800	64	<5	<20	322	0.34	<10	117	<10	28	199

P: 4 ACID DIGEST/ICP-FINISH
 3: 4 ACID DIGEST/AA-FINISH

l/nw
 td2299s
 _S/07


 ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2293R

Revised

14-Mar-08

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

Attention: Bob Singh

No. of samples received: 106

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-164

Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-19751	0.10	0.003
2	S07-19752	0.04	0.001
3	S07-19753	<0.03	<0.001
4	S07-19754	<0.03	<0.001
5	S07-19755	<0.03	<0.001
6	S07-19756	0.05	0.001
7	S07-19757	0.09	0.003
8	S07-19758	0.10	0.003
9	S07-19759	0.03	0.001
10	S07-19760	0.17	0.005
11	S07-19761	0.15	0.004
12	S07-19762	0.14	0.004
13	S07-19763	0.11	0.003
14	S07-19764	* <0.03	<0.001
15	S07-19765	0.08	0.002
16	S07-19766	0.08	0.002
17	S07-19767	<0.03	<0.001
18	S07-19768	<0.03	<0.001
19	S07-19769	<0.03	<0.001
20	S07-19770	<0.03	<0.001
21	S07-19771	<0.03	<0.001
22	S07-19772	0.03	0.001
23	S07-19773	0.19	0.006
24	S07-19774	0.04	0.001
25	S07-19775	0.08	0.002
26	S07-19776	0.25	0.007
27	S07-19777	<0.03	<0.001
28	S07-19778	* 6.59	0.192

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

* = 30g FA

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	S07-19779	<0.03	<0.001
30	S07-19780	<0.03	<0.001
31	S07-19781	<0.03	<0.001
32	S07-19782	0.27	0.008
33	S07-19783	<0.03	<0.001
34	S07-19784	0.06	0.002
35	S07-19785	0.31	0.009
36	S07-19786	0.08	0.002
37	S07-19787	<0.03	<0.001
38	S07-19788	0.09	0.003
39	S07-19789	0.23	0.007
40	S07-19790	0.19	0.006
41	S07-19791	0.39	0.011
42	S07-19792	0.37	0.011
43	S07-19793	0.04	0.001
44	S07-19794	0.10	0.003
45	S07-19795	0.05	0.001
46	S07-19796	<0.03	<0.001
47	S07-19797	<0.03	<0.001
48	S07-19798	<0.03	<0.001
49	S07-19799	<0.03	<0.001
50	S07-19800	<0.03	<0.001
51	S07-19801	<0.03	<0.001
52	S07-19802	<0.03	<0.001
53	S07-19803	<0.03	<0.001
54	S07-19804	0.15	0.005
55	S07-19805	<0.03	<0.001
56	S07-19806	<0.03	<0.001
57	S07-19807	<0.03	<0.001
58	S07-19808	<0.03	<0.001
59	S07-19809	<0.03	<0.001
60	S07-19810	<0.03	<0.001
61	S07-19811	<0.03	<0.001
62	S07-19812	<0.03	<0.001
63	S07-19813	<0.03	<0.001
64	S07-19814	<0.03	<0.001
65	S07-19815	<0.03	<0.001
66	S07-19816	<0.03	<0.001
67	S07-19817	2.00	0.058
68	S07-19818	<0.03	<0.001
69	S07-19819	0.04	0.001
70	S07-19820	0.05	0.001
71	S07-19821	0.46	0.013
72	S07-19822	4.21	0.123

* = 30g FA



ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #		Au (g/t)	Au (oz/t)
73	S07-19823	*	6.63	0.193
74	S07-19824		<0.03	<0.001
75	S07-19825		0.09	0.003
76	S07-19826		<0.03	<0.001
77	S07-19827		0.05	0.002
78	S07-19828		0.16	0.005
79	S07-19829		0.71	0.021
80	S07-19830		1.26	0.037
81	S07-19831		0.03	0.001
82	S07-19832		0.07	0.002
83	S07-19833		2.93	0.085
84	S07-19834		2.72	0.079
85	S07-19835		0.61	0.018
86	S07-19836		3.65	0.106
87	S07-19837		0.66	0.019
88	S07-19838		0.99	0.029
89	S07-19839		<0.03	<0.001
90	S07-19840		0.04	0.001
91	S07-19841		0.10	0.003
92	S07-19842		<0.03	<0.001
93	S07-19843	*	<0.03	<0.001
94	S07-19844		<0.03	<0.001
95	S07-19845		0.03	0.001
96	S07-19846		<0.03	<0.001
97	S07-19847		0.06	0.002
98	S07-19848		<0.03	<0.001
99	S07-19849		0.75	0.022
100	S07-19850		0.84	0.025
101	S07-19851		0.05	0.002
102	S07-19852		<0.03	<0.001
103	S07-19853		0.05	0.001
104	S07-19854		0.46	0.013
105	S07-19855		0.05	0.002
106	S07-19856		<0.03	<0.001

QC DATA:Resplit:

1	S07-19751	0.13	0.004
36	S07-19786	0.08	0.002
71	S07-19821	0.40	0.012
106	S07-19856	<0.03	<0.001

* = 30g FA


ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

CO TECH LABORATORY LTD.
 1041 Dallas Drive
 AMLOOPS, B.C.
 2C 6T4

ICP CERTIFICATE OF ANALYSIS - AK 2007-2293R

Revised

Skygold Ventures
 615 - 800 W. Pender Street
 Vancouver, BC
 V6B 2V6

Phone: 250-573-5700
 Fax: 250-573-4557

No. of samples received: 106
 Sample Type: Core
 Project: Spanish Mountain
 Shipment #: SMC-07-164
 Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-19751	1.4	4.60	20	185	<5	3.27	2	21	279	101	4.32	1.82	20	1.57	926	22	0.10	99	550	36	10	<20	139	0.07	<10	169	<10	7	197
2	S07-19752	0.2	4.89	35	190	<5	3.70	1	28	488	96	5.67	1.93	20	3.10	1124	31	0.18	146	760	34	10	<20	179	0.08	<10	225	<10	7	191
3	S07-19753	0.4	4.60	30	375	<5	4.04	1	34	600	80	5.26	1.57	10	4.26	1440	18	0.28	213	610	28	10	<20	182	0.08	<10	184	<10	6	207
4	S07-19754	0.4	5.04	50	405	<5	3.77	1	42	789	85	5.67	1.75	<10	5.04	1475	12	0.33	262	610	32	10	<20	189	0.08	<10	184	<10	5	235
5	S07-19755	0.8	4.34	20	200	<5	3.33	1	23	264	77	4.29	1.57	20	2.30	1003	25	0.34	82	790	26	<5	<20	189	0.08	<10	209	<10	7	168
6	S07-19756	0.8	4.73	25	170	<5	4.19	1	25	463	81	5.22	1.74	20	2.68	1284	29	0.32	119	680	34	10	<20	220	0.08	<10	218	<10	9	184
7	S07-19757	1.0	5.25	25	175	<5	3.74	2	24	365	132	5.09	1.89	20	1.92	1080	30	0.22	95	770	40	10	<20	214	0.09	<10	236	<10	8	223
8	S07-19758	0.8	5.95	15	245	<5	2.52	2	16	248	69	3.73	1.77	20	1.39	855	22	0.87	48	870	32	5	<20	183	0.12	<10	194	<10	8	172
9	S07-19759	0.4	5.80	15	305	<5	3.55	<1	12	203	70	3.11	1.59	10	1.72	960	5	1.11	22	610	28	<5	<20	212	0.11	<10	128	<10	9	100
10	S07-19760	1.6	4.69	20	165	<5	2.92	3	21	249	108	5.06	1.72	20	1.46	919	39	0.32	81	810	44	10	<20	148	0.07	<10	250	<10	7	292
11	S07-19761	1.6	5.10	20	160	<5	3.42	3	20	258	92	5.60	1.84	20	1.52	1084	46	0.27	88	890	54	15	<20	143	0.08	<10	264	<10	7	331
12	S07-19762	1.4	4.46	20	205	<5	2.46	3	18	204	87	4.63	1.70	20	1.19	877	35	0.14	68	750	42	10	<20	111	0.08	<10	220	<10	6	270
13	S07-19763	2.2	4.73	20	160	<5	2.61	3	21	350	78	4.96	1.74	20	1.28	938	41	0.09	74	920	42	10	<20	116	0.12	<10	275	<10	9	275
14	S07-19764	<0.2	0.08	<5	35	<5	>10	<1	<1	2	3	0.57	0.02	<10	>10	200	<1	0.01	2	170	8	<5	<20	40	<0.01	<10	3	<10	<1	16
15	S07-19765	0.4	6.08	15	410	<5	4.16	<1	13	109	87	3.21	1.74	10	1.74	943	17	1.20	26	750	24	<5	<20	190	0.13	<10	138	<10	10	107
16	S07-19766	0.6	5.69	10	585	<5	3.83	<1	10	135	74	2.91	1.56	10	1.91	1039	2	0.98	19	540	28	<5	<20	220	0.11	<10	115	<10	9	82
17	S07-19767	0.6	4.91	15	210	<5	1.79	1	16	234	70	3.64	1.29	10	1.29	483	5	1.22	27	400	26	<5	<20	120	0.10	<10	133	<10	6	152
18	S07-19768	0.4	5.50	15	295	<5	2.24	<1	14	171	64	3.69	1.52	10	1.48	646	5	1.18	26	450	26	<5	<20	133	0.11	<10	134	<10	7	120
19	S07-19769	0.4	5.40	10	750	<5	2.42	<1	11	143	72	2.49	1.67	10	1.36	653	4	1.07	27	460	28	<5	<20	137	0.12	<10	138	<10	7	127
20	S07-19770	0.6	5.36	10	825	<5	2.22	<1	10	195	66	2.86	1.62	20	1.40	620	6	0.98	27	470	24	<5	<20	128	0.13	<10	145	<10	6	122
21	S07-19771	0.2	5.53	5	935	<5	2.20	<1	11	153	66	2.89	1.79	20	1.42	591	9	1.09	26	500	28	<5	<20	124	0.13	<10	166	<10	6	122
22	S07-19772	0.2	7.10	15	430	<5	2.82	<1	13	115	63	3.49	2.11	20	1.54	711	61	0.95	22	590	34	<5	<20	141	0.13	<10	151	<10	8	107
23	S07-19773	0.6	6.13	15	735	<5	1.84	1	19	171	101	4.27	1.82	20	1.34	504	18	0.86	44	610	36	<5	<20	114	0.14	<10	246	<10	6	193
24	S07-19774	0.4	5.86	10	830	<5	1.77	2	14	180	87	4.05	1.76	20	1.37	495	16	0.98	42	600	32	<5	<20	112	0.12	<10	265	<10	5	220
25	S07-19775	0.4	7.21	20	430	<5	2.18	2	21	164	124	4.82	2.00	20	1.43	573	28	1.09	63	740	36	<5	<20	120	0.13	<10	315	<10	6	301
26	S07-19776	0.4	6.91	15	1060	<5	2.24	1	16	180	92	4.31	1.87	20	1.60	585	20	1.13	38	870	34	<5	<20	131	0.13	<10	208	<10	7	176
27	S07-19777	0.2	7.35	20	1255	<5	2.11	<1	18	133	73	4.65	1.75	10	1.86	612	3	1.10	23	680	38	<5	<20	128	0.14	<10	160	<10	6	115
28	S07-19778	5.5	3.89	120	305	<5	0.41	<1	7	45	59	3.68	2.79	<10	0.23	228	8	0.49	21	370	28	65	<20	81	0.30	<10	51	<10	11	54
29	S07-19779	0.2	7.18	15	1030	<5	1.84	<1	20	115	71	4.58	1.85	10	1.89	632	2	1.56	24	620	38	<5	<20	133	0.14	<10	137	<10	5	132
30	S07-19780	0.4	6.49	10	1060	<5	1.53	<1	13	78	47	3.53	1.89	10	1.64	526	4	1.24	18	530	30	<5	<20	131	0.16	<10	144	<10	6	121

Et #.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
31	S07-19781	0.4	4.83	10	455	<5	2.20	<1	9	143	47	2.76	1.23	20	1.21	568	5	1.11	16	430	30	<5	<20	130	0.11	<10	85	<10	6	93
32	S07-19782	0.4	5.61	20	85	<5	1.92	<1	21	91	73	5.22	1.85	10	1.25	458	25	0.61	37	520	32	<5	<20	121	0.11	<10	162	<10	7	110
33	S07-19783	0.4	6.94	15	1245	<5	1.73	<1	9	106	56	3.24	2.28	20	1.58	547	8	0.79	17	500	30	<5	<20	136	0.14	<10	113	<10	7	102
34	S07-19784	0.6	6.71	15	1070	<5	1.95	<1	9	82	65	3.11	2.30	20	1.49	558	6	0.52	18	520	30	<5	<20	142	0.14	<10	142	<10	7	107
35	S07-19785	0.4	7.25	15	1065	<5	2.44	<1	10	123	73	3.03	2.63	20	1.45	681	3	0.40	15	640	34	<5	<20	136	0.18	<10	131	<10	7	105
36	S07-19786	0.4	7.27	15	515	<5	3.42	<1	14	100	77	4.73	2.36	20	1.63	1230	1	1.04	12	1160	38	<5	<20	179	0.21	<10	125	<10	9	109
37	S07-19787	0.2	6.98	15	715	<5	3.38	<1	13	102	44	4.72	2.01	20	1.67	1244	<1	1.56	11	1110	30	<5	<20	202	0.21	<10	100	<10	9	99
38	S07-19788	<0.2	7.51	15	680	<5	4.02	<1	19	100	55	4.93	2.19	20	1.72	1288	<1	1.47	17	940	30	<5	<20	229	0.22	<10	143	<10	9	82
39	S07-19789	<0.2	6.49	10	610	<5	3.39	<1	14	99	56	4.26	1.96	10	1.49	1075	<1	1.34	14	710	28	<5	<20	204	0.19	<10	115	<10	8	67
40	S07-19790	0.6	7.47	20	295	<5	4.15	<1	20	101	91	5.41	2.06	10	1.41	1117	<1	1.82	16	770	34	<5	<20	235	0.20	<10	167	<10	8	101
41	S07-19791	0.6	6.76	30	285	<5	2.29	<1	13	131	74	3.87	2.33	20	0.89	748	42	1.07	19	570	28	<5	<20	144	0.17	<10	150	<10	7	54
42	S07-19792	0.4	6.58	15	680	<5	1.79	<1	12	108	63	3.59	2.36	20	0.99	748	46	1.03	11	570	26	<5	<20	139	0.16	<10	81	<10	6	59
43	S07-19793	0.2	7.39	15	1060	<5	2.33	<1	15	102	53	4.43	2.71	20	1.51	1094	1	0.73	18	630	34	<5	<20	153	0.18	<10	108	<10	6	104
44	S07-19794	0.2	7.79	15	895	<5	2.92	<1	18	104	81	5.24	2.98	20	1.83	1484	<1	0.68	18	660	30	<5	<20	185	0.18	<10	168	<10	6	72
45	S07-19795	0.6	7.40	15	720	<5	3.15	<1	23	148	128	5.19	2.81	10	1.95	1473	<1	0.63	22	500	190	<5	<20	220	0.16	<10	192	<10	4	66
46	S07-19796	<0.2	0.09	<5	45	<5	>10	<1	<1	2	3	0.55	0.02	<10	>10	183	<1	0.01	3	160	8	<5	<20	39	<0.01	<10	2	<10	<1	15
47	S07-19797	<0.2	7.79	15	585	<5	3.02	<1	23	74	49	5.49	2.07	10	2.06	1473	<1	1.94	22	580	30	<5	<20	236	0.18	<10	206	<10	4	112
48	S07-19798	<0.2	7.15	15	445	<5	3.50	<1	19	92	79	4.72	1.50	10	1.79	1325	<1	2.44	29	970	30	<5	<20	279	0.18	<10	185	<10	7	83
49	S07-19799	<0.2	7.01	15	530	<5	2.92	<1	15	105	63	3.81	1.38	10	1.40	984	<1	2.12	21	500	28	<5	<20	308	0.17	<10	119	<10	5	60
50	S07-19800	<0.2	6.58	15	455	<5	2.98	<1	15	96	70	3.93	1.06	10	1.54	1088	<1	2.04	21	500	26	<5	<20	333	0.15	<10	124	<10	5	69
51	S07-19801	<0.2	7.99	15	665	<5	3.65	<1	19	85	60	4.31	1.37	10	1.73	1160	<1	2.38	23	700	32	<5	<20	365	0.20	<10	184	<10	4	76
52	S07-19802	0.2	8.33	20	920	<5	3.90	<1	20	97	112	4.87	1.94	10	1.58	981	<1	1.82	25	860	34	<5	<20	324	0.21	<10	221	<10	5	88
53	S07-19803	0.4	7.59	20	435	<5	3.49	<1	21	95	133	5.74	1.32	<10	1.58	942	3	1.77	24	660	32	<5	<20	307	0.18	<10	194	<10	5	64
54	S07-19804	<0.2	7.65	20	850	<5	2.92	<1	17	105	130	4.75	2.85	10	1.65	869	<1	0.47	20	730	46	<5	<20	144	0.22	<10	170	<10	6	142
55	S07-19805	0.2	7.65	15	795	<5	3.06	<1	15	78	114	4.53	2.61	10	1.64	916	<1	0.96	19	680	34	<5	<20	160	0.19	<10	165	<10	5	67
56	S07-19806	<0.2	9.22	20	1085	<5	4.38	<1	19	78	71	4.81	2.80	20	1.94	1164	<1	1.03	24	1090	34	<5	<20	262	0.20	<10	169	<10	6	55
57	S07-19807	0.2	7.01	15	915	<5	3.46	<1	12	94	71	3.44	1.50	10	1.37	836	<1	1.70	17	710	28	<5	<20	284	0.20	<10	158	<10	5	61
58	S07-19808	<0.2	7.30	20	795	<5	3.52	<1	16	107	64	4.16	1.41	10	1.36	875	<1	1.38	19	800	32	<5	<20	364	0.17	<10	147	<10	5	56
59	S07-19809	<0.2	7.74	25	765	<5	3.73	<1	20	91	68	4.61	1.28	10	1.82	1035	<1	1.28	23	770	32	<5	<20	338	0.18	<10	192	<10	5	58
60	S07-19810	<0.2	8.33	20	550	<5	4.02	<1	24	72	117	5.32	0.92	10	2.29	1172	<1	1.41	22	730	32	<5	<20	349	0.24	<10	194	<10	6	73
61	S07-19811	<0.2	8.44	15	515	<5	3.52	<1	18	68	142	5.41	0.77	10	2.43	1076	<1	1.46	21	750	36	<5	<20	327	0.23	<10	183	<10	5	70
62	S07-19812	<0.2	8.39	15	650	<5	2.83	<1	20	60	95	5.05	0.93	10	2.02	989	<1	2.48	19	770	32	<5	<20	277	0.26	<10	182	<10	6	87
63	S07-19813	<0.2	7.40	10	745	<5	3.53	<1	15	73	77	4.25	1.05	<10	1.63	1016	2	2.17	16	680	28	<5	<20	306	0.20	<10	185	<10	5	50
64	S07-19814	<0.2	8.42	15	1100	<5	3.37	<1	19	107	122	5.04	0.99	10	1.92	1134	<1	2.19	20	810	30	<5	<20	317	0.22	<10	203	<10	6	76
65	S07-19815	<0.2	8.44	15	775	<5	3.58	<1	23	109	40	5.32	1.27	10	2.06	1172	<1	1.76	21	1060	36	<5	<20	365	0.23	<10	218	<10	6	75
66	S07-19816	<0.2	8.37	15	930	<5	3.83	<1	21	195	112	4.94	1.66	10	1.82	1119	<1	1.21	20	730	38	<5	<20	384	0.23	<10	199	<10	5	81
67	S07-19817	4.9	4.41	105	320	<5	0.49	1	13	35	631	5.21	2.37	10	1.66	396	10	0.24	24	460	94	50	<20	59	0.29	<10	57	<10	12	668
68	S07-19818	0.2	8.80	20	1090	<5	3.93	<1	19	70	87	4.48	2.55	10	1.75	1197	<1	0.97	17	860	34	<5	<20	329	0.25	<10	199	<10	5	71
69	S07-19819	<0.2	8.10	20	515	<5	4.58	<1	17	79	61	4.34	1.89	10	1.80	1204	<1	1.39	19	770	30	<5	<20	323	0.25	<10	165	<10	5	65
70	S07-19820	0.2	7.77	15	890	<5	4.17	<1	12	172	65	3.81	2.41	20	1.54	979	<1	0.67	13	650	30	<5	<20	326	0.23	<10	114	<10	11	56

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Li%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
71	S07-19821	0.4	5.10	10	280	<5	3.56	<1	8	146	61	2.51	1.11	<10	1.09	774	<1	2.40	11	520	100	<5	<20	435	0.12	<10	85	<10	4	61
72	S07-19822	23.0	7.09	10	645	<5	3.92	3	10	161	273	3.01	2.62	20	1.37	935	<1	0.91	14	800	604	<5	<20	393	0.19	<10	105	<10	6	236
73	S07-19823	5.6	3.48	165	300	<5	0.39	<1	6	41	51	3.67	2.98	<10	0.24	222	5	0.49	22	410	18	65	<20	91	0.28	<10	50	<10	10	54
74	S07-19824	0.4	7.51	15	650	<5	3.60	<1	8	62	42	2.89	2.68	20	1.03	740	<1	1.19	10	680	34	<5	<20	284	0.18	<10	75	<10	6	43
75	S07-19825	0.2	7.27	20	715	<5	3.96	<1	14	94	51	3.93	2.98	10	1.84	1060	<1	0.46	19	780	28	<5	<20	324	0.19	<10	155	<10	6	63
76	S07-19826	<0.2	7.17	15	430	<5	3.88	<1	14	110	67	4.42	2.11	10	1.79	1014	<1	2.01	21	1020	28	<5	<20	271	0.20	<10	154	<10	5	58
77	S07-19827	0.6	7.42	20	415	<5	3.80	<1	19	69	226	6.55	2.05	10	2.01	1246	<1	2.04	14	1980	34	<5	<20	336	0.22	<10	224	<10	11	76
78	S07-19828	1.0	6.76	20	575	<5	4.56	<1	27	140	181	6.07	2.32	10	2.49	1598	1	0.72	50	1600	28	<5	<20	301	0.18	<10	189	<10	9	70
79	S07-19829	1.0	7.30	20	745	<5	4.68	<1	18	100	201	6.41	2.59	20	1.85	1395	<1	1.48	13	1860	46	<5	<20	539	0.29	<10	212	<10	11	62
80	S07-19830	0.8	7.35	80	375	<5	4.55	<1	31	78	124	8.04	2.25	10	1.52	1090	2	1.80	17	1870	42	<5	<20	447	0.23	<10	203	<10	9	103
81	S07-19831	0.4	8.08	15	405	<5	5.20	<1	19	51	228	6.53	2.57	20	2.02	1264	<1	0.74	14	1870	36	<5	<20	349	0.28	<10	209	<10	10	76
82	S07-19832	0.6	7.43	15	540	<5	4.42	<1	24	61	196	5.25	2.48	10	1.46	987	<1	1.36	11	1610	28	<5	<20	358	0.20	<10	183	<10	7	52
83	S07-19833	1.4	7.57	30	170	<5	4.22	<1	28	80	123	6.15	2.50	20	1.53	978	<1	2.04	18	1730	46	<5	<20	527	0.23	<10	198	<10	8	32
84	S07-19834	0.6	8.17	35	260	<5	4.63	<1	22	170	128	5.65	2.82	20	1.56	1012	<1	2.12	15	1800	60	<5	<20	553	0.26	<10	231	<10	8	34
85	S07-19835	1.0	7.44	15	530	<5	4.07	<1	20	75	193	5.88	2.21	20	1.62	1041	<1	2.24	13	1710	34	<5	<20	489	0.22	<10	208	<10	9	52
86	S07-19836	0.8	7.38	20	585	<5	4.00	<1	19	72	202	5.50	2.41	10	1.64	1003	<1	1.82	12	1780	30	<5	<20	403	0.26	<10	208	<10	9	71
87	S07-19837	1.2	6.83	25	325	<5	3.99	<1	17	149	160	5.63	2.45	10	1.73	1021	<1	0.62	13	2120	28	<5	<20	407	0.20	<10	181	<10	10	42
88	S07-19838	1.0	7.14	20	555	<5	3.73	<1	21	191	289	6.12	2.38	20	1.65	1247	<1	1.73	14	1840	32	<5	<20	419	0.26	<10	230	<10	9	49
89	S07-19839	0.6	6.57	15	270	<5	3.82	<1	18	58	212	5.85	1.13	20	1.57	1183	<1	3.32	11	1910	28	<5	<20	468	0.27	<10	206	<10	11	76
90	S07-19840	0.6	7.13	15	400	<5	3.62	<1	21	37	196	6.07	1.54	20	1.75	1274	<1	3.31	13	1940	30	<5	<20	479	0.29	<10	218	<10	10	77
91	S07-19841	1.2	6.59	15	375	<5	3.30	<1	10	107	101	3.69	1.15	20	1.44	892	<1	3.29	14	820	34	<5	<20	420	0.20	<10	111	<10	8	52
92	S07-19842	<0.2	7.60	20	1075	<5	3.54	<1	16	114	73	4.71	2.65	<10	2.18	1213	<1	1.78	20	720	26	<5	<20	438	0.15	<10	171	<10	4	86
93	S07-19843	<0.2	0.08	<5	20	<5	>10	<1	<1	2	2	0.49	0.02	<10	>10	180	<1	0.02	2	150	<2	<5	<20	47	<0.01	<10	2	<10	<1	11
94	S07-19844	0.2	7.00	15	680	<5	3.15	<1	14	77	73	3.96	2.11	10	1.45	930	<1	2.43	17	850	28	<5	<20	417	0.18	<10	141	<10	5	61
95	S07-19845	<0.2	7.74	20	670	<5	3.46	<1	15	138	56	4.14	2.20	10	1.78	1031	<1	1.92	13	740	28	<5	<20	445	0.20	<10	159	<10	4	37
96	S07-19846	<0.2	7.93	20	835	<5	4.77	<1	22	185	63	5.57	2.82	<10	2.66	1382	<1	0.80	35	920	54	<5	<20	521	0.19	<10	203	<10	5	102
97	S07-19847	0.4	7.38	15	670	<5	3.44	<1	11	54	112	4.30	2.16	<10	1.72	1108	<1	2.28	15	750	30	<5	<20	386	0.20	<10	166	<10	4	53
98	S07-19848	0.2	7.08	15	540	<5	3.03	<1	13	81	43	3.92	1.73	10	1.40	1000	<1	3.01	12	750	28	<5	<20	443	0.18	<10	120	<10	5	56
99	S07-19849	<0.2	6.78	15	520	<5	2.60	4	13	140	51	3.87	1.82	<10	1.30	881	<1	2.63	14	700	28	<5	<20	406	0.15	<10	119	<10	4	381
100	S07-19850	0.6	7.15	15	610	<5	3.41	<1	11	115	65	3.76	1.91	10	1.28	776	<1	2.49	13	750	30	<5	<20	350	0.18	<10	107	<10	7	41
101	S07-19851	<0.2	8.14	20	740	<5	3.86	<1	17	131	34	4.27	2.19	10	1.73	1120	<1	2.45	15	750	30	<5	<20	357	0.21	<10	144	<10	5	57
102	S07-19852	0.2	7.92	15	835	<5	3.14	<1	17	92	68	4.64	2.44	<10	1.91	1030	<1	1.90	18	720	30	<5	<20	280	0.19	<10	178	<10	3	68
103	S07-19853	<0.2	7.41	20	570	<5	4.06	<1	16	191	60	4.18	1.93	10	1.75	1235	<1	2.56	21	790	30	<5	<20	366	0.20	<10	144	<10	7	43
104	S07-19854	0.2	7.85	20	795	<5	3.55	<1	18	79	78	4.83	3.00	<10	2.11	1235	<1	0.90	25	870	28	<5	<20	224	0.20	<10	191	<10	4	65
105	S07-19855	0.2	8.01	20	560	<5	3.30	<1	21	143	114	5.24	2.48	<10	2.59	1117	<1	0.79	24	1010	30	<5	<20	268	0.20	<10	186	<10	5	62
106	S07-19856	0.4	8.15	30	485	<5	3.78	<1	23	116	184	5.37	2.30	10	3.25	1215	<1	0.51	23	990	30	<5	<20	341	0.26	<10	211	<10	6	57


IC DATA:


repeat:	Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Li%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn	
1	S07-19751	1.4	4.21	20	175	<5	3.46	2	20	285	98	4.01	1.74	20	1.61	900	21	0.09	98	520	38	10	<20	145	0.07	<10	169	<10	6	182
10	S07-19760	1.4	4.88	20	225	<5	3.10	3	21	244	105	5.19	1.71	20	1.45	951	40	0.32	82	840	48	15	<20	147	0.08	<10	249	<10	7	293
19	S07-19769	0.6	5.31	10	780	<5	2.39	<1	11	143	71	2.50	1.70	20	1.36	633	4	1.12	26	460	30	<5	<20	136	0.13	<10	141	<10	6	126
36	S07-19786	0.2	6.99	20	495	<5	3.23	<1	13	101	79	4.47	2.42	20	1.60	1142	1	1.05	12	1090	36	<5	<20	172	0.19	<10	123	<10	9	99
45	S07-19795	0.6	7.34	15	725	<5	3.12	<1	21	148	128	5.00	2.74	<10	1.97	1464	<1	0.61	21	500	182	<5	<20	222	0.17	<10	196	<10	5	67
54	S07-19804	<0.2	7.82	20	850	<5	3.00	<1	17	104	133	4.61	2.87	10	1.68	887	<1	0.48	20	740	48	<5	<20	147	0.21	<10	169	<10	5	141

Et #.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Li%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
71	S07-19821	0.6	5.72	10	295	<5	3.48	<1	8	128	63	2.82	1.16	<10	1.19	840	<1	2.57	12	560	110	<5	<20	464	0.15	<10	91	<10	5	66
80	S07-19830	0.8	7.09	60	300	<5	4.24	<1	32	81	120	7.78	2.31	20	1.54	1068	2	1.85	17	1820	44	<5	<20	452	0.21	<10	207	<10	8	104
89	S07-19839	0.8	6.80	20	280	<5	3.92	<1	19	58	227	6.14	1.19	20	1.62	1228	<1	3.43	11	1990	26	<5	<20	484	0.31	<10	218	<10	13	74
106	S07-19856	0.5	8.05	25	480	<5	3.76	<1	22	110	180	5.27	2.23	10	3.18	1188	<1	0.49	23	960	30	<5	<20	335	0.26	<10	209	<10	7	55
split:																														
1	S07-19751	1.2	4.71	20	170	<5	3.23	2	21	263	90	4.47	1.90	20	1.60	939	24	0.10	94	600	42	10	<20	142	0.10	<10	174	<10	7	186
36	S07-19786	0.4	7.16	15	525	<5	3.31	<1	13	101	88	4.33	2.35	20	1.61	1146	2	1.00	12	1080	40	<5	<20	174	0.21	<10	128	<10	9	101
71	S07-19821	0.7	6.10	15	315	<5	3.73	<1	11	143	65	3.30	1.36	10	1.33	837	<1	2.37	16	590	142	<5	<20	472	0.16	<10	98	<10	6	71
106	S07-19856	0.4	8.26	20	495	<5	3.81	<1	22	97	191	5.56	2.36	10	3.28	1172	<1	0.51	24	990	32	<5	<20	329	0.24	<10	215	<10	6	60
standard:																														
sd3		0.6	5.78	25	1415	<5	2.49	<1	17	63	40	4.38	1.36	40	1.30	2606	7	1.12	34	1690	56	<5	<20	265	0.36	<10	118	<10	33	205
sd3		0.4	5.85	25	1365	<5	2.51	<1	17	61	42	4.19	1.39	30	1.29	2547	6	1.14	32	1660	56	<5	<20	258	0.34	<10	119	<10	32	207
sd3		0.6	5.52	25	1225	<5	2.58	<1	14	56	34	3.77	1.46	30	1.32	2466	4	1.25	31	1710	56	<5	<20	254	0.31	<10	105	<10	27	192
sd3		0.4	5.59	30	1235	<5	2.44	<1	14	57	35	3.97	1.49	30	1.33	2474	5	1.29	32	1730	58	5	<20	265	0.32	<10	110	<10	28	195

P: 4 ACID DIGEST/ICP-FINISH
 G: 4 ACID DIGEST/AA-FINISH

l/nw
 /td2293as/
 LS/07


 ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer



ASSAYING, GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING
ISO 9001 Accredited Co.

10041 Dallas Drive, Kamloops, BC V2C 6T4
Phone (250) 573-5700 Fax (250) 573-4557
E-mail: info@ecotechlab.com
www.ecotechlab.com

CERTIFICATE OF ASSAY AK 2007- 2293

Skygold Ventures
615-800 W. Pender Street
VANCOUVER, BC

14-Mar-08

Attention: Bob Singh

No. of samples received: 106
Sample Type: Core
Project: Spanish Mountain
Shipment #: SMC-07-164
Samples submitted by: Tasha Gainer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	S07-19751	0.10	0.003
2	S07-19752	0.04	0.001
3	S07-19753	<0.03	<0.001
4	S07-19754	<0.03	<0.001
5	S07-19755	<0.03	<0.001
6	S07-19756	0.05	0.001
7	S07-19757	0.09	0.003
8	S07-19758	0.10	0.003
9	S07-19759	0.03	0.001
10	S07-19760	0.17	0.005
11	S07-19761	0.15	0.004
12	S07-19762	0.14	0.004
13	S07-19763	0.11	0.003
14	S07-19764	<0.03	<0.001
15	S07-19765	0.08	0.002
16	S07-19766	0.08	0.002
17	S07-19767	<0.03	<0.001
18	S07-19768	<0.03	<0.001
19	S07-19769	<0.03	<0.001
20	S07-19770	<0.03	<0.001
21	S07-19771	<0.03	<0.001
22	S07-19772	0.03	0.001
23	S07-19773	0.19	0.006
24	S07-19774	0.04	0.001
25	S07-19775	0.08	0.002
26	S07-19776	0.25	0.007
27	S07-19777	<0.03	<0.001
28	S07-19778	6.59	0.192

* = 30g FA

Jutta Jealouse
ECOTECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
29	S07-19779	<0.03	<0.001
30	S07-19780	<0.03	<0.001
31	S07-19781	<0.03	<0.001
32	S07-19782	0.27	0.008
33	S07-19783	<0.03	<0.001
34	S07-19784	0.06	0.002
35	S07-19785	0.31	0.009
36	S07-19786	0.08	0.002
37	S07-19787	<0.03	<0.001
38	S07-19788	0.09	0.003
39	S07-19789	0.23	0.007
40	S07-19790	0.19	0.006
41	S07-19791	0.39	0.011
42	S07-19792	0.37	0.011
43	S07-19793	0.04	0.001
44	S07-19794	0.10	0.003
45	S07-19795	0.05	0.001
46	S07-19796	<0.03	<0.001
47	S07-19797	<0.03	<0.001
48	S07-19798	<0.03	<0.001
49	S07-19799	<0.03	<0.001
50	S07-19800	<0.03	<0.001
51	S07-19801	<0.03	<0.001
52	S07-19802	<0.03	<0.001
53	S07-19803	<0.03	<0.001
54	S07-19804	0.15	0.005
55	S07-19805	<0.03	<0.001
56	S07-19806	<0.03	<0.001
57	S07-19807	<0.03	<0.001
58	S07-19808	<0.03	<0.001
59	S07-19809	<0.03	<0.001
60	S07-19810	<0.03	<0.001
61	S07-19811	<0.03	<0.001
62	S07-19812	<0.03	<0.001
63	S07-19813	<0.03	<0.001
64	S07-19814	<0.03	<0.001
65	S07-19815	<0.03	<0.001
66	S07-19816	<0.03	<0.001
67	S07-19817	2.00	0.058
68	S07-19818	<0.03	<0.001
69	S07-19819	0.04	0.001
70	S07-19820	0.05	0.001
71	S07-19821	0.46	0.013
72	S07-19822	4.21	0.123

= 30g FA

Adam Brockner
ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
73	S07-19823	6.63	0.193
74	S07-19824	<0.03	<0.001
75	S07-19825	0.09	0.003
76	S07-19826	<0.03	<0.001
77	S07-19827	0.05	0.002
78	S07-19828	0.16	0.005
79	S07-19829	0.71	0.021
80	S07-19830	1.26	0.037
81	S07-19831	0.03	0.001
82	S07-19832	0.07	0.002
83	S07-19833	2.93	0.085
84	S07-19834	2.72	0.079
85	S07-19835	0.61	0.018
86	S07-19836	3.65	0.106
87	S07-19837	0.66	0.019
88	S07-19838	0.99	0.029
89	S07-19839	<0.03	<0.001
90	S07-19840	0.04	0.001
91	S07-19841	0.10	0.003
92	S07-19842	<0.03	<0.001
93	S07-19843	<0.03	<0.001
94	S07-19844	<0.03	<0.001
95	S07-19845	0.03	0.001
96	S07-19846	<0.03	<0.001
97	S07-19847	0.06	0.002
98	S07-19848	<0.03	<0.001
99	S07-19849	0.75	0.022
100	S07-19850	0.84	0.025
101	S07-19851	0.05	0.002
102	S07-19852	<0.03	<0.001
103	S07-19853	0.05	0.001
104	S07-19854	0.46	0.013
105	S07-19855	0.05	0.002
106	S07-19856	<0.03	<0.001

QC DATA:**Resplit:**

1	S07-19751	0.13	0.004
36	S07-19786	0.08	0.002
71	S07-19821	0.40	0.012
106	S07-19856	<0.03	<0.001

* = 30g FA

ECO TECH LABORATORY LTD.

Jutta Jealouse

B.C. Certified Assayer


Metallic Assays

ET #.	Tag #	Au (g/t)	Au (oz/t)
Standard:			
	OXI54	1.90	0.055
	OXI54	1.82	0.053
	OXI54	1.86	0.054
	OXI54	1.88	0.055
	OXI54	1.84	0.054
	OXI54	1.90	0.055
	OXI54	1.82	0.053
	OXI54	1.86	0.054
	OXI54	1.87	0.055

1 KG METALLIC SCREEN, FIRE ASSAY, AA - FINISH

* = 30g FA

JJ/nw
XLS/07


ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

DO TECH LABORATORY LTD.

1041 Dallas Drive

AMLOOPS, B.C.

BC 6T4

Phone: 250-573-5700

Fax: 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2007-2293

Skygold Ventures

615 - 800 W. Pender Street

Vancouver, BC

V6B 2V6

No. of samples received: 106

Sample Type: Core

Project: Spanish Mountain

Shipment #: SMC-07-164

Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S07-19751	1.4	4.60	20	185	<5	3.27	2	21	279	101	4.32	1.82	20	1.57	926	22	0.10	99	550	36	10	<20	139	0.07	<10	169	<10	7	197
2	S07-19752	0.2	4.89	35	190	<5	3.70	1	28	488	96	5.67	1.93	20	3.10	1124	31	0.18	146	760	34	10	<20	179	0.08	<10	225	<10	7	191
3	S07-19753	0.4	4.60	30	375	<5	4.04	1	34	600	80	5.26	1.57	10	4.26	1440	18	0.28	213	610	28	10	<20	182	0.08	<10	184	<10	6	207
4	S07-19754	0.4	5.04	50	405	<5	3.77	1	42	789	85	5.67	1.75	<10	5.04	1475	12	0.33	262	610	32	10	<20	189	0.08	<10	184	<10	5	235
5	S07-19755	0.8	4.34	20	200	<5	3.33	1	23	264	77	4.29	1.57	20	2.30	1003	25	0.34	82	790	26	<5	<20	189	0.08	<10	209	<10	7	168
6	S07-19756	0.8	4.73	25	170	<5	4.19	1	25	463	81	5.22	1.74	20	2.68	1284	29	0.32	119	680	34	10	<20	220	0.08	<10	218	<10	9	184
7	S07-19757	1.0	5.25	25	175	<5	3.74	2	24	365	132	5.09	1.89	20	1.92	1080	30	0.22	95	770	40	10	<20	214	0.09	<10	236	<10	8	223
8	S07-19758	0.8	5.95	15	245	<5	2.52	2	16	248	69	3.73	1.77	20	1.39	855	22	0.87	48	870	32	5	<20	183	0.12	<10	194	<10	8	172
9	S07-19759	0.4	5.80	15	305	<5	3.55	<1	12	203	70	3.11	1.59	10	1.72	960	5	1.11	22	610	28	<5	<20	212	0.11	<10	128	<10	9	100
10	S07-19760	1.6	4.69	20	165	<5	2.92	3	21	249	108	5.06	1.72	20	1.46	919	39	0.32	81	810	44	10	<20	148	0.07	<10	250	<10	7	292
11	S07-19761	1.6	5.10	20	160	<5	3.42	3	20	258	92	5.60	1.84	20	1.52	1084	46	0.27	88	890	54	15	<20	143	0.08	<10	264	<10	7	331
12	S07-19762	1.4	4.46	20	205	<5	2.46	3	18	204	87	4.63	1.70	20	1.19	877	35	0.14	68	750	42	10	<20	111	0.08	<10	220	<10	6	270
13	S07-19763	2.2	4.73	20	160	<5	2.61	3	21	350	78	4.96	1.74	20	1.28	938	41	0.09	74	920	42	10	<20	116	0.12	<10	275	<10	9	275
14	S07-19764	<0.2	0.08	<5	35	<5	>10	<1	<1	2	3	0.57	0.02	<10	>10	200	<1	0.01	2	170	8	<5	<20	40	<0.01	<10	3	<10	<1	16
15	S07-19765	0.4	6.08	15	410	<5	4.16	<1	13	109	87	3.21	1.74	10	1.74	943	17	1.20	26	750	24	<5	<20	190	0.13	<10	138	<10	10	107
16	S07-19766	0.6	5.69	10	585	<5	3.83	<1	10	135	74	2.91	1.56	10	1.91	1039	2	0.98	19	540	28	<5	<20	220	0.11	<10	115	<10	9	82
17	S07-19767	0.6	4.91	15	210	<5	1.79	1	16	234	70	3.64	1.29	10	1.29	483	5	1.22	27	400	26	<5	<20	120	0.10	<10	133	<10	6	152
18	S07-19768	0.4	5.50	15	295	<5	2.24	<1	14	171	64	3.69	1.52	10	1.48	646	5	1.18	26	450	26	<5	<20	133	0.11	<10	134	<10	7	120
19	S07-19769	0.4	5.40	10	750	<5	2.42	<1	11	143	72	2.49	1.67	10	1.36	653	4	1.07	27	460	28	<5	<20	137	0.12	<10	138	<10	7	127
20	S07-19770	0.6	5.36	10	825	<5	2.22	<1	10	195	66	2.86	1.62	20	1.40	620	6	0.98	27	470	24	<5	<20	128	0.13	<10	145	<10	6	122
21	S07-19771	0.2	5.53	5	935	<5	2.20	<1	11	153	66	2.89	1.79	20	1.42	591	9	1.09	26	500	28	<5	<20	124	0.13	<10	166	<10	6	122
22	S07-19772	0.2	7.10	15	430	<5	2.82	<1	13	115	63	3.49	2.11	20	1.54	711	61	0.95	22	590	34	<5	<20	141	0.13	<10	151	<10	8	107
23	S07-19773	0.6	6.13	15	735	<5	1.84	1	19	171	101	4.27	1.82	20	1.34	504	18	0.86	44	610	36	<5	<20	114	0.14	<10	246	<10	6	193
24	S07-19774	0.4	5.86	10	830	<5	1.77	2	14	180	87	4.05	1.76	20	1.37	495	16	0.98	42	600	32	<5	<20	112	0.12	<10	265	<10	5	220
25	S07-19775	0.4	7.21	20	430	<5	2.18	2	21	164	124	4.82	2.00	20	1.43	573	28	1.09	63	740	36	<5	<20	120	0.13	<10	315	<10	6	301
26	S07-19776	0.4	6.91	15	1060	<5	2.24	1	16	180	92	4.31	1.87	20	1.60	585	20	1.13	38	870	34	<5	<20	131	0.13	<10	208	<10	7	176
27	S07-19777	0.2	7.35	20	1255	<5	2.11	<1	18	133	73	4.65	1.75	10	1.86	612	3	1.10	23	680	38	<5	<20	128	0.14	<10	160	<10	6	115
28	S07-19778	5.5	3.89	120	305	<5	0.41	<1	7	45	59	3.68	2.79	<10	0.23	228	8	0.49	21	370	28	65	<20	81	0.30	<10	51	<10	11	54
29	S07-19779	0.2	7.18	15	1030	<5	1.84	<1	20	115	71	4.58	1.85	10	1.89	632	2	1.56	24	620	38	<5	<20	133	0.14	<10	137	<10	5	132
30	S07-19780	0.4	6.49	10	1060	<5	1.53	<1	13	78	47	3.53	1.89	Page 64	526	4	1.24	18	530	30	<5	<20	131	0.16	<10	144	<10	6	121	

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
31	S07-19781	0.4	4.83	10	455	<5	2.20	<1	9	143	47	2.76	1.23	20	1.21	568	5	1.11	16	430	30	<5	<20	130	0.11	<10	85	<10	6	93
32	S07-19782	0.4	5.61	20	85	<5	1.92	<1	21	91	73	5.22	1.85	10	1.25	458	25	0.61	37	520	32	<5	<20	121	0.11	<10	162	<10	7	110
33	S07-19783	0.4	6.94	15	1245	<5	1.73	<1	9	106	56	3.24	2.28	20	1.58	547	8	0.79	17	500	30	<5	<20	136	0.14	<10	113	<10	7	102
34	S07-19784	0.6	6.71	15	1070	<5	1.95	<1	9	82	65	3.11	2.30	20	1.49	558	6	0.52	18	520	30	<5	<20	142	0.14	<10	142	<10	7	107
35	S07-19785	0.4	7.25	15	1065	<5	2.44	<1	10	123	73	3.03	2.63	20	1.45	681	3	0.40	15	640	34	<5	<20	136	0.18	<10	131	<10	7	105
36	S07-19786	0.4	7.27	15	515	<5	3.42	<1	14	100	77	4.73	2.36	20	1.63	1230	1	1.04	12	1160	38	<5	<20	179	0.21	<10	125	<10	9	109
37	S07-19787	0.2	6.98	15	715	<5	3.38	<1	13	102	44	4.72	2.01	20	1.67	1244	<1	1.56	11	1110	30	<5	<20	202	0.21	<10	100	<10	9	99
38	S07-19788	<0.2	7.51	15	680	<5	4.02	<1	19	100	55	4.93	2.19	20	1.72	1288	<1	1.47	17	940	30	<5	<20	229	0.22	<10	143	<10	9	82
39	S07-19789	<0.2	6.49	10	610	<5	3.39	<1	14	99	56	4.26	1.96	10	1.49	1075	<1	1.34	14	710	28	<5	<20	204	0.19	<10	115	<10	8	67
40	S07-19790	0.6	7.47	20	295	<5	4.15	<1	20	101	91	5.41	2.06	10	1.41	1117	<1	1.82	16	770	34	<5	<20	235	0.20	<10	167	<10	8	101
41	S07-19791	0.6	6.76	30	285	<5	2.29	<1	13	131	74	3.87	2.33	20	0.89	748	42	1.07	19	570	28	<5	<20	144	0.17	<10	150	<10	7	54
42	S07-19792	0.4	6.58	15	680	<5	1.79	<1	12	108	63	3.59	2.36	20	0.99	748	46	1.03	11	570	26	<5	<20	139	0.16	<10	81	<10	6	59
43	S07-19793	0.2	7.39	15	1060	<5	2.33	<1	15	102	53	4.43	2.71	20	1.51	1094	1	0.73	18	630	34	<5	<20	153	0.18	<10	108	<10	6	104
44	S07-19794	0.2	7.79	15	895	<5	2.92	<1	18	104	81	5.24	2.98	20	1.83	1484	<1	0.68	18	660	30	<5	<20	185	0.18	<10	168	<10	6	72
45	S07-19795	0.6	7.40	15	720	<5	3.15	<1	23	148	128	5.19	2.81	10	1.95	1473	<1	0.63	22	500	190	<5	<20	220	0.16	<10	192	<10	4	66
46	S07-19796	<0.2	0.09	<5	45	<5	>10	<1	<1	2	3	0.55	0.02	<10	>10	183	<1	0.01	3	160	8	<5	<20	39	<0.01	<10	2	<10	<1	15
47	S07-19797	<0.2	7.79	15	585	<5	3.02	<1	23	74	49	5.49	2.07	10	2.06	1473	<1	1.94	22	580	30	<5	<20	236	0.18	<10	206	<10	4	112
48	S07-19798	<0.2	7.15	15	445	<5	3.50	<1	19	92	79	4.72	1.50	10	1.79	1325	<1	2.44	29	970	30	<5	<20	279	0.18	<10	185	<10	7	83
49	S07-19799	<0.2	7.01	15	530	<5	2.92	<1	15	105	63	3.81	1.38	10	1.40	984	<1	2.12	21	500	28	<5	<20	308	0.17	<10	119	<10	5	60
50	S07-19800	<0.2	6.58	15	455	<5	2.98	<1	15	96	70	3.93	1.06	10	1.54	1088	<1	2.04	21	500	26	<5	<20	333	0.15	<10	124	<10	5	69
51	S07-19801	<0.2	7.99	15	665	<5	3.65	<1	19	85	60	4.31	1.37	10	1.73	1160	<1	2.38	23	700	32	<5	<20	365	0.20	<10	184	<10	4	76
52	S07-19802	0.2	8.33	20	920	<5	3.90	<1	20	97	112	4.87	1.94	10	1.58	981	<1	1.82	25	860	34	<5	<20	324	0.21	<10	221	<10	5	88
53	S07-19803	0.4	7.59	20	435	<5	3.49	<1	21	95	133	5.74	1.32	<10	1.58	942	3	1.77	24	660	32	<5	<20	307	0.18	<10	194	<10	5	64
54	S07-19804	<0.2	7.65	20	850	<5	2.92	<1	17	105	130	4.75	2.85	10	1.65	869	<1	0.47	20	730	46	<5	<20	144	0.22	<10	170	<10	6	142
55	S07-19805	0.2	7.65	15	795	<5	3.06	<1	15	78	114	4.53	2.61	10	1.64	916	<1	0.96	19	680	34	<5	<20	160	0.19	<10	165	<10	5	67
56	S07-19806	<0.2	9.22	20	1085	<5	4.38	<1	19	78	71	4.81	2.80	20	1.94	1164	<1	1.03	24	1090	34	<5	<20	262	0.20	<10	169	<10	6	55
57	S07-19807	0.2	7.01	15	915	<5	3.46	<1	12	94	71	3.44	1.50	10	1.37	836	<1	1.70	17	710	28	<5	<20	284	0.20	<10	158	<10	5	61
58	S07-19808	<0.2	7.30	20	795	<5	3.52	<1	16	107	64	4.16	1.41	10	1.36	875	<1	1.38	19	800	32	<5	<20	364	0.17	<10	147	<10	5	56
59	S07-19809	<0.2	7.74	25	765	<5	3.73	<1	20	91	68	4.61	1.28	10	1.82	1035	<1	1.28	23	770	32	<5	<20	338	0.18	<10	192	<10	5	58
60	S07-19810	<0.2	8.33	20	550	<5	4.02	<1	24	72	117	5.32	0.92	10	2.29	1172	<1	1.41	22	730	32	<5	<20	349	0.24	<10	194	<10	6	73
61	S07-19811	<0.2	8.44	15	515	<5	3.52	<1	18	68	142	5.41	0.77	10	2.43	1076	<1	1.46	21	750	36	<5	<20	327	0.23	<10	183	<10	5	70
62	S07-19812	<0.2	8.39	15	650	<5	2.83	<1	20	60	95	5.05	0.93	10	2.02	989	<1	2.48	19	770	32	<5	<20	277	0.26	<10	182	<10	6	87
63	S07-19813	<0.2	7.40	10	745	<5	3.53	<1	15	73	77	4.25	1.05	<10	1.63	1016	2	2.17	16	680	28	<5	<20	306	0.20	<10	185	<10	5	50
64	S07-19814	<0.2	8.42	15	1100	<5	3.37	<1	19	107	122	5.04	0.99	10	1.92	1134	<1	2.19	20	810	30	<5	<20	317	0.22	<10	203	<10	6	76
65	S07-19815	<0.2	8.44	15	775	<5	3.58	<1	23	109	40	5.32	1.27	10	2.06	1172	<1	1.76	21	1060	36	<5	<20	365	0.23	<10	218	<10	6	75
66	S07-19816	<0.2	8.37	15	930	<5	3.83	<1	21	195	112	4.94	1.66	10	1.82	1119	<1	1.21	20	730	38	<5	<20	384	0.23	<10	199	<10	5	81
67	S07-19817	4.9	4.41	105	320	<5	0.49	1	13	35	631	5.21	2.37	10	1.66	396	10	0.24	24	460	94	50	<20	59	0.29	<10	57	<10	12	668
68	S07-19818	0.2	8.80	20	1090	<5	3.93	<1	19	70	87	4.48	2.55	10	1.75	1197	<1	0.97	17	860	34	<5	<20	329	0.25	<10	199	<10	5	71
69	S07-19819	<0.2	8.10	20	515	<5	4.58	<1	17	79	61	4.34	1.89	10	1.80	1204	<1	1.39	19	770	30	<5	<20	323	0.25	<10	165	<10	5	65
70	S07-19820	0.2	7.77	15	890	<5	4.17	<1	12	172	65	3.81	2.41	20	1.54	979	<1	0.67	13	650	30	<5	<20	326	0.23	<10	114	<10	11	56

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	Y	Zn		
71	SO7-19821	0.4	5.10	10	280	<5	3.56	<1	8	146	61	2.51	1.11	<10	1.09	774	<1	2.40	11	520	100	<5	<20	435	0.12	<10	85	<10	4	61
72	SO7-19822	23.0	7.09	10	645	<5	3.92	3	10	161	273	3.01	2.62	20	1.37	935	<1	0.91	14	800	604	<5	<20	393	0.19	<10	105	<10	6	236
73	SO7-19823	5.6	3.48	165	300	<5	0.39	<1	6	41	51	3.67	2.98	<10	0.24	222	5	0.49	22	410	18	65	<20	91	0.28	<10	50	<10	10	54
74	SO7-19824	0.4	7.51	15	650	<5	3.60	<1	8	62	42	2.89	2.68	20	1.03	740	<1	1.19	10	680	34	<5	<20	284	0.18	<10	75	<10	6	43
75	SO7-19825	0.2	7.27	20	715	<5	3.96	<1	14	94	51	3.93	2.98	10	1.84	1060	<1	0.46	19	780	28	<5	<20	324	0.19	<10	155	<10	6	63
76	SO7-19826	<0.2	7.17	15	430	<5	3.88	<1	14	110	67	4.42	2.11	10	1.79	1014	<1	2.01	21	1020	28	<5	<20	271	0.20	<10	154	<10	5	58
77	SO7-19827	0.6	7.42	20	415	<5	3.80	<1	19	69	226	6.55	2.05	10	2.01	1246	<1	2.04	14	1980	34	<5	<20	336	0.22	<10	224	<10	11	76
78	SO7-19828	1.0	6.76	20	575	<5	4.56	<1	27	140	181	6.07	2.32	10	2.49	1598	1	0.72	50	1600	28	<5	<20	301	0.18	<10	189	<10	9	70
79	SO7-19829	1.0	7.30	20	745	<5	4.68	<1	18	100	201	6.41	2.59	20	1.85	1395	<1	1.48	13	1860	46	<5	<20	539	0.29	<10	212	<10	11	62
80	SO7-19830	0.8	7.35	80	375	<5	4.55	<1	31	78	124	8.04	2.25	10	1.52	1090	2	1.80	17	1870	42	<5	<20	447	0.23	<10	203	<10	9	103
81	SO7-19831	0.4	8.08	15	405	<5	5.20	<1	19	51	228	6.53	2.57	20	2.02	1264	<1	0.74	14	1870	36	<5	<20	349	0.28	<10	209	<10	10	76
82	SO7-19832	0.6	7.43	15	540	<5	4.42	<1	24	61	196	5.25	2.48	10	1.46	987	<1	1.36	11	1610	28	<5	<20	358	0.20	<10	183	<10	7	52
83	SO7-19833	1.4	7.57	30	170	<5	4.22	<1	28	80	123	6.15	2.50	20	1.53	978	<1	2.04	18	1730	46	<5	<20	527	0.23	<10	198	<10	8	32
84	SO7-19834	0.6	8.17	35	260	<5	4.63	<1	22	170	128	5.65	2.82	20	1.56	1012	<1	2.12	15	1800	60	<5	<20	553	0.26	<10	231	<10	8	34
85	SO7-19835	1.0	7.44	15	530	<5	4.07	<1	20	75	193	5.88	2.21	20	1.62	1041	<1	2.24	13	1710	34	<5	<20	489	0.22	<10	208	<10	9	52
86	SO7-19836	0.8	7.38	20	585	<5	4.00	<1	19	72	202	5.50	2.41	10	1.64	1003	<1	1.82	12	1780	30	<5	<20	403	0.26	<10	208	<10	9	71
87	SO7-19837	1.2	6.83	25	325	<5	3.99	<1	17	149	160	5.63	2.45	10	1.73	1021	<1	0.62	13	2120	28	<5	<20	407	0.20	<10	181	<10	10	42
88	SO7-19838	1.0	7.14	20	555	<5	3.73	<1	21	191	289	6.12	2.38	20	1.65	1247	<1	1.73	14	1840	32	<5	<20	419	0.26	<10	230	<10	9	49
89	SO7-19839	0.6	6.57	15	270	<5	3.82	<1	18	58	212	5.85	1.13	20	1.57	1183	<1	3.32	11	1910	28	<5	<20	468	0.27	<10	206	<10	11	76
90	SO7-19840	0.6	7.13	15	400	<5	3.62	<1	21	37	196	6.07	1.54	20	1.75	1274	<1	3.31	13	1940	30	<5	<20	479	0.29	<10	218	<10	10	77
91	SO7-19841	1.2	6.59	15	375	<5	3.30	<1	10	107	101	3.69	1.15	20	1.44	892	<1	3.29	14	820	34	<5	<20	420	0.20	<10	111	<10	8	52
92	SO7-19842	<0.2	7.60	20	1075	<5	3.54	<1	16	114	73	4.71	2.65	<10	2.18	1213	<1	1.78	20	720	26	<5	<20	438	0.15	<10	171	<10	4	86
93	SO7-19843	<0.2	0.08	<5	20	<5	>10	<1	<1	2	2	0.49	0.02	<10	>10	180	<1	0.02	2	150	<2	<5	<20	47	<0.01	<10	2	<10	<1	11
94	SO7-19844	0.2	7.00	15	680	<5	3.15	<1	14	77	73	3.96	2.11	10	1.45	930	<1	2.43	17	850	28	<5	<20	417	0.18	<10	141	<10	5	61
95	SO7-19845	<0.2	7.74	20	670	<5	3.46	<1	15	138	56	4.14	2.20	10	1.78	1031	<1	1.92	13	740	28	<5	<20	445	0.20	<10	159	<10	4	37
96	SO7-19846	<0.2	7.93	20	835	<5	4.77	<1	22	185	63	5.57	2.82	<10	2.66	1382	<1	0.80	35	920	54	<5	<20	521	0.19	<10	203	<10	5	102
97	SO7-19847	0.4	7.38	15	670	<5	3.44	<1	11	54	112	4.30	2.16	<10	1.72	1108	<1	2.28	15	750	30	<5	<20	386	0.20	<10	166	<10	4	53
98	SO7-19848	0.2	7.08	15	540	<5	3.03	<1	13	81	43	3.92	1.73	10	1.40	1000	<1	3.01	12	750	28	<5	<20	443	0.18	<10	120	<10	5	56
99	SO7-19849	<0.2	6.78	15	520	<5	2.60	4	13	140	51	3.87	1.82	<10	1.30	881	<1	2.63	14	700	28	<5	<20	406	0.15	<10	119	<10	4	381
100	SO7-19850	0.6	7.15	15	610	<5	3.41	<1	11	115	65	3.76	1.91	10	1.28	776	<1	2.49	13	750	30	<5	<20	350	0.18	<10	107	<10	7	41
101	SO7-19851	<0.2	8.14	20	740	<5	3.86	<1	17	131	34	4.27	2.19	10	1.73	1120	<1	2.45	15	750	30	<5	<20	357	0.21	<10	144	<10	5	57
102	SO7-19852	0.2	7.92	15	835	<5	3.14	<1	17	92	68	4.64	2.44	<10	1.91	1030	<1	1.90	18	720	30	<5	<20	280	0.19	<10	178	<10	3	68
103	SO7-19853	<0.2	7.41	20	570	<5	4.06	<1	16	191	60	4.18	1.93	10	1.75	1235	<1	2.56	21	790	30	<5	<20	366	0.20	<10	144	<10	7	43
104	SO7-19854	0.2	7.85	20	795	<5	3.55	<1	18	79	78	4.83	3.00	<10	2.11	1235	<1	0.90	25	870	28	<5	<20	224	0.20	<10	191	<10	4	65
105	SO7-19855	0.2	8.01	20	560	<5	3.30	<1	21	143	114	5.24	2.48	<10	2.59	1117	<1	0.79	24	1010	30	<5	<20	268	0.20	<10	186	<10	5	62
106	SO7-19856	0.4	8.15	30	485	<5	3.78	<1	23	116	184	5.37	2.30	10	3.25	1215	<1	0.51	23	990	30	<5	<20	341	0.26	<10	211	<10	6	57

IC DATA:

Repeat:

1	SO7-19751	1.4	4.21	20	175	<5	3.46	2	20	285	98	4.01	1.74	20	1.61	900	21	0.09	98	520	38	10	<20	145	0.07	<10	169	<10	6	182
10	SO7-19760	1.4	4.88	20	225	<5	3.10	3	21	244	105	5.19	1.71	20	1.45	951	40	0.32	82	840	48	15	<20	147	0.08	<10	249	<10	7	293
19	SO7-19769	0.6	5.31	10	780	<5	2.39	<1	11	143	71	2.50	1.70	20	1.36	633	4	1.12	26	460	30	<5	<20	136	0.13	<10	141	<10	6	126
36	SO7-19786	0.2	6.99	20	495	<5	3.23	<1	13	101	79	4.47	2.42	20	1.60	1142	1	1.05	12	1090	36	<5	<20	172	0.19	<10	123	<10	9	99
45	SO7-19795	0.6	7.34	15	725	<5	3.12	<1	21	148	128	5.00	2.74	<10	1.97	1464	<1	0.61	21	500	182	<5	<20	222	0.17	<10	196	<10	5	67
54	SO7-19804	<0.2	7.82	20	850	<5	3.00	<1	17	104	133	4.61	2.87	10	1.68	887	<1	0.48	20	740	48	<5	<20	147	0.21	<10	169	<10	5	141

Et #.	Tag	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	Y	Zn			
71	SO7-19821	0.6	5.72	10	295	<5	3.48	<1	8	128	63	2.82	1.16	<10	1.19	840	<1	2.57	12	560	110	<5	<20	464	0.15	<10	91	<10	5	66
80	SO7-19830	0.8	7.09	60	300	<5	4.24	<1	32	81	120	7.78	2.31	20	1.54	1068	2	1.85	17	1820	44	<5	<20	452	0.21	<10	207	<10	8	104
89	SO7-19839	0.8	6.80	20	280	<5	3.92	<1	19	58	227	6.14	1.19	20	1.62	1228	<1	3.43	11	1990	26	<5	<20	484	0.31	<10	218	<10	13	74
106	SO7-19856	0.5	8.05	25	480	<5	3.76	<1	22	110	180	5.27	2.23	10	3.18	1188	<1	0.49	23	960	30	<5	<20	335	0.26	<10	209	<10	7	55
iesplit:																														
1	S07-19751	1.2	4.71	20	170	<5	3.23	2	21	263	90	4.47	1.90	20	1.60	939	24	0.10	94	600	42	10	<20	142	0.10	<10	174	<10	7	186
36	S07-19786	0.4	7.16	15	525	<5	3.31	<1	13	101	88	4.33	2.35	20	1.61	1146	2	1.00	12	1080	40	<5	<20	174	0.21	<10	128	<10	9	101
71	SO7-19821	0.7	6.10	15	315	<5	3.73	<1	11	143	65	3.30	1.36	10	1.33	837	<1	2.37	16	590	142	<5	<20	472	0.16	<10	98	<10	6	71
106	SO7-19856	0.4	8.26	20	495	<5	3.81	<1	22	97	191	5.56	2.36	10	3.28	1172	<1	0.51	24	990	32	<5	<20	329	0.24	<10	215	<10	6	60
standard:																														
tsd3		0.6	5.78	25	1415	<5	2.49	<1	17	63	40	4.38	1.36	40	1.30	2606	7	1.12	34	1690	56	<5	<20	265	0.36	<10	118	<10	33	205
tsd3		0.4	5.85	25	1365	<5	2.51	<1	17	61	42	4.19	1.39	30	1.29	2547	6	1.14	32	1660	56	<5	<20	258	0.34	<10	119	<10	32	207
tsd3		0.6	5.52	25	1225	<5	2.58	<1	14	56	34	3.77	1.46	30	1.32	2466	4	1.25	31	1710	56	<5	<20	254	0.31	<10	105	<10	27	192
tsd3		0.4	5.59	30	1235	<5	2.44	<1	14	57	35	3.97	1.49	30	1.33	2474	5	1.29	32	1730	58	5	<20	265	0.32	<10	110	<10	28	195

DP: 4 ACID DIGEST/ICP-FINISH
 G: 4 ACID DIGEST/AA-FINISH

J/nw
 /td2293as/
 LS/07

Jutta Jealouse
 ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

10-Jul-07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK7-0702
Total Digestion

Mincord Exploration
110-325 Howe Street
Vancouver, BC
V6C 1Z7

Phone: 250-573-5700
Fax : 250-573-4557

Attention: Bill Morton

No. of samples received: 13

Sample type: RC Chips

Project #: Spanish Mountain

Shipment #: SMR-07-002

Samples Submitted by: Johnston

Values in ppm unless otherwise reported

Tag #	Shipno	Certificate	Au (g/t)	Ag	Al %	As	Ba	BI	Ca %	Cd	Co	Cr	Cu	Fe %	K%	La	Mg %	Mn	Mo	Na %	NI	P	Pb	Sb	Sn	Sr	TI %	U	V	W	Y	Zn
D130889	SMR-07-002	AK7-0702	<0.03	<0.2	9.25	15	715	5	0.1	<1	13	118	14	5.11	2.81	30	0.19	389	2	0.97	28	790	28	<5	<20	112	0.39	<10	110	<10	8	112
D130890	SMR-07-002	AK7-0702	<0.03	0.4	4.67	25	450	<5	0.09	<1	11	134	32	2.88	1.21	20	0.22	114	9	0.67	31	1020	24	<5	<20	49	0.23	<10	155	<10	9	113
D130891	SMR-07-002	AK7-0702	0.03	0.2	4.37	15	605	<5	0.06	<1	10	143	40	1.77	1.31	20	0.26	79	5	0.24	48	400	24	<5	<20	38	0.22	<10	81	<10	6	103
D130892	SMR-07-002	AK7-0702	0.07	0.4	>10	25	1185	10	0.94	<1	11	440	122	5.86	3.1	40	0.36	119	20	2.02	41	>10000	38	5	<20	256	0.31	<10	368	<10	18	107
D130893	SMR-07-002	AK7-0702	<0.03	<0.2	7.37	20	1315	5	5.52	<1	26	287	20	4.74	3.28	30	4.42	1087	<1	0.58	113	1220	34	<5	<20	282	0.15	<10	200	<10	11	66
D130894	SMR-07-002	AK7-0702	<0.03	<0.2	4.7	5	340	5	0.12	<1	8	189	23	4.25	0.99	20	0.09	280	2	0.89	25	630	26	<5	<20	133	0.21	<10	59	<10	6	101
D130895	SMR-07-002	AK7-0702	<0.03	<0.2	3.54	10	305	<5	0.03	<1	8	177	20	3.14	0.86	10	0.08	187	2	0.35	24	380	20	<5	<20	104	0.15	<10	49	<10	3	133
D130896	SMR-07-002	AK7-0702	<0.03	<0.2	8.98	30	930	<5	0.16	1	16	152	27	4.71	2.28	30	0.17	411	3	1.19	45	680	30	<5	<20	178	0.33	<10	126	<10	5	191
D130897	SMR-07-002	AK7-0702	<0.03	0.2	9.9	<5	1105	10	1.3	<1	55	288	62	5.33	3.83	20	0.87	362	<1	0.63	88	2380	26	5	<20	101	0.65	<10	244	<10	13	108
D130898	SMR-07-002	AK7-0702	0.38	1.4	5.03	70	750	<5	0.03	1	3	185	29	3	1.58	20	0.23	218	25	0.38	13	610	82	20	<20	29	0.27	<10	271	<10	5	92
D130899	SMR-07-002	AK7-0702	<0.03	0.2	4.84	40	970	<5	1.39	2	6	109	155	2.46	1.58	20	0.8	588	3	0.59	35	650	30	<5	<20	80	0.25	<10	90	<10	7	145
D130900	SMR-07-002	AK7-0702	<0.03	<0.2	3.3	25	555	<5	2.6	2	8	115	10	1.99	0.93	20	0.62	849	2	0.62	29	1250	12	<5	<20	107	0.14	<10	131	<10	8	194
D130901	SMR-07-002	AK7-0702	<0.03	<0.2	4.11	5	615	<5	4.8	<1	5	72	15	2.25	1.15	20	2.18	881	2	0.8	21	690	14	<5	<20	224	0.18	<10	110	<10	7	120
RES-D130889	SMR-07-002	AK7-0702	<0.03	<0.2	9.06	15	730	5	0.1	<1	12	136	15	5.29	2.85	30	0.19	390	2	1.03	29	790	28	<5	<20	117	0.34	<10	114	<10	5	115
RE-D130889	SMR-07-002	AK7-0702		<0.2	9.55	15	745	5	0.11	<1	12	141	15	5.27	2.9	30	0.2	395	2	1.03	29	820	28	<5	<20	119	0.35	<10	116	<10	6	114

ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

13-Jul-07

ICP CERTIFICATE OF ANALYSIS AK07-0748

Mincord Exploration
110-325 Howe Street
Vancouver, BC
V6C 1Z7

Attention: Bill Morton

No. of samples received: 43
Sample type: Rock
Project #: Spanish Mountain
Shipment #: SMR-07-03
Samples Submitted by: Johnston

Tag #	Shipno	Certificate	Au (g/t)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
D130902	SMR-07-03	AK07-0748MIN	<0.03	0.4	0.26	45	75	5	0.05	2	12	116	79	4.81	<10	<0.01	116	29	0.03	33	460	20	10	<20	14	0.02	<10	24	<10	7	166
D130903	SMR-07-03	AK07-0748MIN	<0.03	<0.2	1.22	10	95	<5	0.13	<1	6	185	22	1.75	<10	1.02	370	2	0.05	13	200	32	<5	<20	8	0.02	<10	17	<10	9	33
D130904	SMR-07-03	AK07-0748MIN	<0.03	<0.2	2.62	15	230	10	0.18	1	10	94	37	3.4	10	2.41	1224	6	0.03	19	320	56	25	<20	6	0.03	<10	21	<10	7	66
D130905	SMR-07-03	AK07-0748MIN	<0.03	<0.2	1.89	15	130	5	0.36	<1	11	84	24	2.63	<10	1.87	557	5	0.03	20	270	46	20	<20	18	0.03	<10	31	<10	7	45
D130906	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.4	35	135	15	2.18	2	15	68	35	5.75	<10	0.28	1688	7	0.08	54	1510	10	5	<20	47	0.04	<10	21	<10	17	82
D130907	SMR-07-03	AK07-0748MIN	0.06	<0.2	0.22	35	240	5	0.71	<1	7	263	48	2.4	<10	0.01	782	3	0.05	27	590	10	<5	<20	37	0.02	<10	6	<10	5	21
D130908	SMR-07-03	AK07-0748MIN	<0.03	0.2	0.55	30	140	10	0.4	2	19	66	71	4.88	<10	0.03	1248	22	0.06	27	950	26	<5	<20	26	0.03	<10	15	<10	8	105
D130909	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.02	10	30	<5	0.06	<1	3	281	8	0.66	<10	<0.01	102	2	0.01	10	80	4	<5	<20	13	<0.01	<10	3	<10	4	20
D130910	SMR-07-03	AK07-0748MIN	<0.03	0.5	0.26	95	80	<5	1.24	1	10	74	46	2.02	<10	0.15	565	2	0.02	54	230	24	<5	<20	24	0.01	<10	5	<10	9	94
D130911	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.26	95	85	5	0.04	1	6	86	76	2.18	<10	0.03	227	3	0.01	48	190	16	<5	<20	10	0.01	<10	6	<10	3	80
D130912	SMR-07-03	AK07-0748MIN	<0.03	0.6	0.03	10	30	<5	0.01	<1	2	228	10	0.59	<10	0.01	92	3	<0.01	8	40	218	<5	<20	7	<0.01	<10	3	<10	1	44
D130913	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.08	20	30	<5	0.04	<1	4	235	16	0.9	<10	<0.01	196	4	<0.01	16	110	16	<5	<20	11	<0.01	<10	6	<10	3	32
D130914	SMR-07-03	AK07-0748MIN	0.09	0.7	0.05	25	35	<5	0.13	1	4	318	18	1.17	<10	<0.01	208	4	<0.01	14	70	150	<5	<20	15	<0.01	<10	4	<10	4	82
D130915	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.04	10	25	<5	0.03	<1	2	227	6	0.55	<10	<0.01	93	<1	0.01	6	50	6	<5	<20	9	<0.01	<10	2	<10	2	2
D130916	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.68	90	100	15	1.74	2	57	87	49	7.6	<10	1.2	1883	5	0.08	174	1180	16	<5	<20	51	0.05	<10	35	<10	10	98
D130917	SMR-07-03	AK07-0748MIN	<0.03	<0.2	2.1	45	85	10	1.22	2	42	125	56	5.8	<10	2.11	1497	5	0.02	121	1040	44	15	<20	29	0.04	<10	64	<10	10	66
D130918	SMR-07-03	AK07-0748MIN	<0.03	<0.2	2.33	50	100	15	1.22	2	40	155	55	5.9	<10	2.29	1562	7	0.05	125	1040	48	20	<20	35	0.04	<10	70	<10	10	70
D130919	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.31	35	135	<5	0.07	1	13	74	52	3.01	<10	0.03	1963	3	0.03	31	260	18	<5	<20	13	0.03	<10	7	<10	5	49
D130920	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.05	15	40	5	0.08	<1	4	260	11	0.82	<10	0.01	305	1	0.01	14	150	4	<5	<20	13	<0.01	<10	3	<10	3	3
D130921	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.54	115	100	<5	2.39	2	22	52	56	4.65	<10	0.59	1605	3	0.07	142	1160	18	<5	<20	71	0.03	<10	19	<10	6	61

Tag #	Shipno	Certificate	Au (g/t)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
D130922	SMR-07-03	AK07-0748MIN	<0.03	0.4	0.28	35	150	<5	0.11	2	15	56	57	3.4	<10	0.03	2625	3	0.02	37	240	36	<5	<20	12	0.03	<10	8	<10	4	71
D130923	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.03	15	35	<5	0.02	<1	3	305	10	0.89	<10	0.02	381	3	<0.01	11	30	18	<5	<20	11	<0.01	<10	4	<10	3	3
D130924	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.33	<5	165	5	0.15	1	9	86	16	2.36	<10	0.07	2063	3	0.02	22	370	12	<5	<20	12	0.03	<10	4	<10	4	58
D130925	SMR-07-03	AK07-0748MIN	<0.03	0.7	0.11	20	75	<5	0.02	<1	6	437	67	1.63	<10	0.02	602	3	0.01	14	120	100	<5	<20	14	0.02	<10	4	<10	2	23
D130926	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.29	10	130	5	0.13	<1	9	89	55	2.02	<10	0.04	1939	2	0.02	19	230	16	<5	<20	12	0.02	<10	4	<10	3	42
D130927	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.37	25	205	<5	0.11	1	12	57	47	3.2	<10	0.07	1193	3	0.02	26	310	16	<5	<20	11	0.03	<10	6	<10	1	53
D130928	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.23	25	130	10	0.19	<1	14	103	41	2.26	<10	0.03	1814	3	0.02	28	230	20	<5	<20	16	0.02	<10	5	<10	5	48
D130929	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.27	45	185	<5	0.07	1	15	81	93	3.77	<10	0.08	4280	3	0.03	47	340	32	<5	<20	12	0.05	<10	13	<10	1	63
D130930	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.19	15	250	5	0.12	1	9	66	40	2.59	<10	0.01	1943	2	0.03	24	260	18	<5	<20	14	0.03	<10	5	<10	3	41
D130931	SMR-07-03	AK07-0748MIN	0.28	7.1	0.14	240	60	<5	0.12	2	7	294	510	1.36	<10	<0.01	583	3	0.03	38	350	8	15	<20	26	0.01	<10	5	<10	3	142
D130932	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.26	20	130	5	0.07	1	8	71	23	2.13	10	0.03	2514	2	0.03	17	240	18	<5	<20	9	0.03	<10	4	<10	4	47
D130933	SMR-07-03	AK07-0748MIN	0.03	0.3	0.02	20	55	<5	<0.01	<1	3	244	15	0.84	<10	<0.01	673	2	<0.01	9	50	128	<5	<20	10	0.01	<10	2	<10	2	9
D130934	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.02	25	45	<5	<0.01	<1	3	351	12	0.71	<10	0.01	414	3	<0.01	10	30	52	<5	<20	9	<0.01	<10	3	<10	3	3
D130935	SMR-07-03	AK07-0748MIN	0.12	0.2	0.12	25	120	<5	0.02	<1	5	186	80	1.33	<10	0.01	1702	2	0.01	14	170	42	<5	<20	9	0.02	<10	5	<10	2	25
D130936	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.31	15	165	<5	0.09	<1	13	86	50	3.49	<10	0.05	3232	3	0.02	23	660	14	<5	<20	16	0.04	<10	9	<10	3	69
D130937	SMR-07-03	AK07-0748MIN	<0.03	0.3	0.24	85	165	15	1.2	3	22	90	95	8	<10	0.01	8353	5	0.05	69	3540	32	<5	<20	46	0.09	<10	16	<10	13	110
D130938	SMR-07-03	AK07-0748MIN	<0.03	0.2	0.05	95	50	10	0.03	<1	14	302	35	3.15	<10	<0.01	370	4	<0.01	68	320	168	<5	<20	9	0.02	<10	5	<10	<1	97
D130939	SMR-07-03	AK07-0748MIN	<0.03	0.2	0.05	90	50	5	0.03	2	15	395	38	3.48	<10	<0.01	389	4	<0.01	74	350	188	<5	<20	9	0.02	<10	5	<10	<1	103
D130940	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.25	30	175	<5	0.02	<1	11	49	27	1.97	<10	0.03	2888	2	0.03	18	240	18	<5	<20	14	0.03	<10	8	<10	3	51
D130941	SMR-07-03	AK07-0748MIN	<0.03	0.2	0.1	30	120	10	0.02	<1	9	109	35	2.64	<10	<0.01	2140	2	0.02	19	180	34	<5	<20	16	0.04	<10	5	<10	2	35
D130942	SMR-07-03	AK07-0748MIN	0.08	0.2	0.18	50	270	10	0.26	2	19	80	152	6.67	10	0.02	5432	6	0.03	79	960	14	<5	<20	21	0.07	<10	17	<10	3	89
D130943	SMR-07-03	AK07-0748MIN	0.15	0.2	0.53	90	120	<5	0.54	2	21	34	78	3.8	<10	0.05	1773	4	0.05	81	1500	92	<5	<20	25	0.03	<10	8	<10	2	110
D130944	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.31	30	80	5	0.14	1	8	92	9	1.77	<10	0.02	551	3	0.05	14	660	66	<5	<20	21	0.01	<10	4	<10	<1	51
RESD13090	SMR-07-03	AK07-0748MIN	<0.03	0.4	0.23	35	80	10	0.04	2	12	105	78	4.61	<10	<0.01	115	28	0.03	32	450	24	10	<20	19	0.02	<10	23	<10	8	158
RESD13093	SMR-07-03	AK07-0748MIN	<0.03	0.2	0.23	75	160	5	0.99	4	21	79	91	7.93	<10	0.01	7986	4	0.05	65	3410	26	<5	<20	40	0.09	<10	15	<10	10	104
RED130902	SMR-07-03	AK07-0748MIN	<0.03	0.4	0.26	40	85	15	0.05	3	13	119	83	4.88	<10	<0.01	120	29	0.03	33	480	24	15	<20	19	0.02	<10	24	<10	10	168
RED130911	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.26	85	90	5	0.04	1	6	86	76	2.19	<10	0.03	233	3	0.01	47	200	18	<5	<20	10	0.01	<10	5	<10	3	80
RED13092C	SMR-07-03	AK07-0748MIN	<0.03	<0.2	0.06	15	35	10	0.08	<1	4	267	11	0.87	<10	0.01	319	<1	0.01	15	150	6	<5	<20	13	0.01	<10	3	<10	4	3
RED130937	SMR-07-03	AK07-0748MIN	<0.03	0.3	0.25	80	180	15	1.23	3	23	92	100	8.18	<10	0.01	8169	5	0.05	66	3660	34	<5	<20	51	0.11	<10	17	<10	14	110

ECO TECH LABORATORY LTD.

Jutta Jealouse

B.C. Certified Assayer

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 2007

Mincord Exploration
110-325 Howe Street
Vancouver, BC
V6C 1Z7

Phone: 250-573-5700
Fax : 250-573-4557

Attention: Bill Morton

No. of samples received: 35
Sample type: Rock
Project #: Spanish Mountain
Shipment #: SMR-07-01
Samples Submitted by: Johnston

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	C130854	2.2	0.26	95	55	<5	0.11	2	16	81	88	4.07	<10	<0.01	749	30	0.02	60	910	36	5	<20	6	0.04	<10	14	<10	2	218
2	C130855	0.2	0.12	15	145	<5	0.03	<1	7	64	35	1.96	<10	<0.01	2375	<1	0.01	21	120	48	<5	<20	3	0.05	<10	3	<10	1	55
3	C130856	0.2	1.91	20	100	<5	0.32	<1	9	71	24	4.09	<10	1.24	512	2	0.03	20	580	38	<5	<20	7	0.09	<10	47	<10	3	86
4	C130857	<0.2	2.68	35	95	5	2.73	<1	31	230	73	5.01	<10	2.89	918	7	0.03	129	1760	46	25	<20	78	0.06	<10	81	<10	9	104
5	C130858	0.2	0.22	25	70	<5	0.07	2	16	11	68	3.93	<10	0.02	555	5	0.01	52	500	12	<5	<20	2	0.04	<10	5	<10	<1	206
6	C130859	0.2	0.19	145	70	<5	0.06	<1	16	58	55	3.79	<10	0.01	838	3	0.01	80	640	10	<5	<20	<1	0.04	<10	4	<10	<1	151
7	C130860	<0.2	0.38	65	130	<5	0.05	<1	12	91	47	3.14	<10	0.01	1049	11	0.02	37	640	20	<5	<20	3	0.04	<10	17	<10	<1	128
8	C130861	<0.2	0.12	45	70	10	2.67	<1	4	122	34	2.21	<10	0.57	1292	2	0.01	29	300	8	<5	<20	58	0.04	<10	4	<10	<1	69
9	C130862	<0.2	0.25	30	75	<5	0.07	1	15	47	57	4.64	<10	0.03	396	4	0.01	34	620	12	<5	<20	3	0.04	<10	4	<10	<1	160
10	C130863	<0.2	0.17	30	55	<5	0.04	2	6	116	54	3.83	<10	<0.01	197	8	0.01	23	490	16	<5	<20	<1	0.03	<10	11	<10	<1	257
11	C130864	<0.2	0.23	60	65	<5	0.05	1	14	98	47	3.65	<10	<0.01	442	12	0.01	37	570	18	<5	<20	3	0.04	<10	6	<10	<1	169
12	C130865	0.2	0.22	40	85	5	0.37	2	14	185	31	3.49	<10	0.06	665	7	0.02	39	540	14	<5	<20	11	0.04	<10	6	<10	<1	118
13	C130866	0.2	0.21	40	75	<5	0.88	2	13	121	28	3.19	<10	0.18	814	9	0.02	47	490	16	10	<20	22	0.03	<10	6	<10	<1	100
14	C130867	0.2	0.29	100	80	<5	0.07	1	15	62	63	3.52	<10	<0.01	811	32	0.02	52	820	24	<5	<20	3	0.04	<10	13	<10	<1	219
15	C130868	<0.2	0.19	35	90	<5	3.52	2	9	75	31	2.89	<10	0.88	1114	3	0.02	31	700	12	10	<20	89	0.04	<10	4	<10	2	113
16	C130869	<0.2	0.15	55	90	<5	1.41	2	9	119	11	2.75	<10	0.32	720	3	0.02	39	630	14	5	<20	34	0.03	<10	4	<10	<1	151
17	C130870	<0.2	0.18	85	55	<5	0.05	<1	10	46	32	3.06	<10	<0.01	277	3	0.02	32	430	14	<5	<20	5	0.03	<10	3	<10	<1	104
18	C130871	<0.2	0.25	65	65	<5	0.07	2	13	49	62	4.22	<10	0.04	682	15	0.01	44	670	24	<5	<20	3	0.04	<10	5	<10	<1	208
19	C130872	<0.2	0.26	40	70	<5	0.13	2	20	56	42	4.95	<10	0.04	391	6	0.02	39	870	34	<5	<20	4	0.05	<10	5	<10	<1	193
20	C130873	0.4	0.27	15	85	5	0.11	2	16	37	26	4.39	<10	<0.01	331	3	0.02	50	640	14	<5	<20	5	0.05	<10	4	<10	<1	130
21	C130874	0.4	0.30	25	100	5	0.32	2	20	69	32	4.42	<10	0.01	827	16	0.02	50	880	20	<5	<20	7	0.04	<10	9	<10	<1	216
22	C130875	0.2	1.61	15	80	5	0.27	1	14	105	50	3.53	<10	1.14	777	8	0.01	58	780	38	15	<20	8	0.04	<10	19	<10	<1	131
23	C130876	0.4	0.23	5	95	<5	1.30	2	8	71	80	2.44	<10	0.32	438	8	0.02	38	840	26	5	<20	32	0.03	<10	8	<10	4	127
24	C130877	0.8	0.24	15	80	<5	0.07	1	13	130	58	2.77	<10	<0.01	247	5	0.02	53	400	46	<5	<20	3	0.03	<10	6	<10	<1	121
25	C130878	0.4	0.20	10	85	<5	1.28	<1	9	149	45	2.49	<10	0.29	571	1	0.02	36	600	16	<5	<20	37	0.03	<10	4	<10	2	106
26	C130879	0.3	0.25	<5	70	<5	0.09	2	19	166	42	4.67	<10	<0.01	546	7	0.03	37	710	20	<5	<20	4	0.05	<10	6	<10	<1	121
27	C130880	0.2	0.31	<5	105	<5	0.24	<1	12	137	50	3.04	<10	0.05	571	2	0.02	75	440	14	<5	<20	6	0.04	<10	6	<10	1	150
28	C130881	0.7	0.22	15	85	<5	0.11	1	10	101	60	2.77	<10	<0.01	632	3	0.02	80	230	8	<5	<20	2	0.03	<10	5	<10	<1	196
29	C130882	0.3	0.22	<5	85	<5	0.70	1	11	76	75	2.34	<10	0.11	500	3	0.02	60	440	8	<5	<20	10	0.02	<10	5	<10	2	136
30	C130883	0.2	0.10	10	45	<5	0.03	<1	4	255	25	1.42	<10	<0.01	117	2	0.01	20	160	10	<5	<20	1	0.01	<10	3	<10	<1	43

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
31	C130884	2	0.18	10	70	5	0.02	<1	6	87	60	2.24	<10	<0.01	2	0.02	39	260	8	<5	<20	4	0.02	<10	4	<10	<1	78	
32	C130885	<0.2	0.03	15	10	<5	0.05	<1	2	273	7	0.60	<10	<0.01	<1	<0.01	4	190	4	<5	<20	2	0.02	<10	1	<10	1	11	
33	C130886	0.2	0.59	15	85	<5	1.94	1	24	61	84	6.27	<10	<0.01	267	10	0.02	89	6820	26	<5	<20	84	0.06	<10	13	<10	24	118
34	C130887	0.2	0.18	20	40	<5	0.10	<1	14	162	46	4.08	<10	<0.01	246	2	0.02	20	500	8	<5	<20	5	0.04	<10	3	<10	<1	51
35	C130888	0.4	0.31	15	70	5	0.27	2	18	66	47	5.71	<10	<0.01	216	33	0.02	58	1230	18	<5	<20	18	0.05	<10	17	<10	<1	100

QC DATA:

Resplit:

1	C130854	2.4	0.25	105	65	<5	0.11	2	16	63	89	4.01	<10	<0.01	696	27	0.02	57	910	34	<5	<20	8	0.05	<10	14	<10	3	214
---	---------	-----	------	-----	----	----	------	---	----	----	----	------	-----	-------	-----	----	------	----	-----	----	----	-----	---	------	-----	----	-----	---	-----

Repeat:

1	C130854	2.2	0.24	95	60	<5	0.11	2	16	78	86	3.95	<10	<0.01	729	29	0.02	56	890	36	<5	<20	7	0.04	<10	13	<10	3	216
10	C130863	<0.2	0.19	30	60	<5	0.04	1	6	122	53	3.74	<10	<0.01	190	7	0.02	22	480	16	<5	<20	1	0.04	<10	13	<10	<1	255
19	C130872	0.2	0.27	40	70	5	0.13	2	21	58	45	5.06	<10	0.05	402	7	0.02	42	900	46	<5	<20	4	0.05	<10	6	<10	<1	194

Standard:

Pb113		20.8	0.24	70	40	<5	2.78	42	3	5	2428	1.12	<10	0.11	1584	94	0.02	2	120	6094	30	<20	80	0.02	<10	8	60	<1	7375
-------	--	------	------	----	----	----	------	----	---	---	------	------	-----	------	------	----	------	---	-----	------	----	-----	----	------	-----	---	----	----	------

ECO TECH LABORATORY LTD.

Jutta Jealouse

B.C. Certified Assayer

JJ/ea
df/633
XLS/07

ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 2007- Total Digestion

Mincord Exploration
110-325 Howe Street
Vancouver, BC
V6C 1Z7

Phone: 250-573-5700
Fax : 250-573-4557

Attention: Bill Morton

No. of samples received: 35
Sample type: Rock
Project #: Spanish Mountain
Shipment #: SMR-07-01
Samples Submitted by: Johnston

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K%	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	C130854	2.3	5.29	110	660	5	0.07	3	13	134	95	3.79	1.35	20	0.14	722	27	0.48	48	920	36	10	<20	84	0.09	<10	315	<10	7	211
2	C130855	0.2	3.82	10	2025	<5	0.02	<1	6	82	39	1.90	1.23	10	0.18	2313	2	0.18	21	170	50	<5	<20	29	0.09	<10	47	<10	6	56
3	C130856	<0.2	8.14	15	1070	5	0.44	<1	5	111	32	4.53	1.21	<10	1.56	549	<1	1.77	23	630	24	<5	<20	144	0.46	<10	148	<10	12	104
4	C130857	<0.2	>10	30	895	10	1.25	<1	30	311	72	5.85	1.19	20	3.62	871	<1	3.07	117	1690	30	5	<20	160	0.37	<10	240	<10	11	126
5	C130858	0.2	9.23	35	1570	5	0.04	1	13	83	80	4.02	2.77	30	0.34	541	1	0.88	51	600	30	<5	<20	49	0.33	<10	209	<10	6	200
6	C130859	0.2	6.06	145	990	5	0.03	2	13	126	62	3.61	2.01	20	0.26	775	<1	0.61	68	660	22	<5	<20	33	0.16	<10	102	<10	5	144
7	C130860	0.2	6.97	65	1035	<5	0.04	1	10	181	57	3.33	2.05	20	0.24	1065	9	0.94	37	730	32	5	<20	39	0.19	<10	180	<10	4	132
8	C130861	0.2	3.47	40	480	<5	1.30	1	3	205	40	2.28	1.05	<10	0.70	1238	1	0.54	28	310	16	<5	<20	88	0.13	<10	53	<10	4	70
9	C130862	<0.2	9.69	45	1430	5	0.05	1	12	152	72	4.94	2.96	30	0.38	395	1	1.00	36	760	30	<5	<20	47	0.25	<10	147	<10	5	166
10	C130863	<0.2	5.53	30	825	5	0.03	1	3	194	60	3.67	1.80	20	0.23	185	5	0.51	23	520	22	<5	<20	29	0.21	<10	289	<10	5	245
11	C130864	<0.2	7.74	60	1130	5	0.04	1	11	176	53	3.42	2.40	30	0.27	399	9	0.95	34	600	32	<5	<20	39	0.16	<10	196	<10	4	159
12	C130865	0.2	7.17	45	1000	<5	0.24	1	11	292	36	3.38	2.08	30	0.28	617	5	0.88	36	580	28	<5	<20	50	0.13	<10	121	<10	5	114
13	C130866	0.2	6.07	45	845	<5	0.42	1	11	203	33	3.07	1.77	20	0.37	753	6	0.82	40	530	28	<5	<20	59	0.14	<10	101	<10	5	97
14	C130867	0.3	8.20	105	1165	<5	0.06	2	12	152	71	3.44	2.41	30	0.27	757	29	0.91	46	850	36	<5	<20	36	0.18	<10	308	<10	5	209
15	C130868	<0.2	5.11	25	710	<5	1.78	1	7	150	35	3.14	1.52	20	1.02	1031	<1	0.74	28	650	20	<5	<20	124	0.13	<10	62	<10	5	108
16	C130869	<0.2	3.60	45	465	<5	0.84	1	6	199	12	2.58	0.97	10	0.41	643	<1	0.58	32	570	18	<5	<20	55	0.12	<10	50	<10	5	138
17	C130870	0.2	7.87	85	1100	<5	0.04	1	7	121	36	2.91	2.21	30	0.24	250	2	1.07	32	480	28	<5	<20	42	0.24	<10	124	<10	4	100
18	C130871	<0.2	8.00	75	1135	5	0.05	1	10	116	70	4.20	2.31	30	0.32	655	12	0.96	41	740	36	<5	<20	39	0.21	<10	144	<10	5	202
19	C130872	<0.2	8.85	50	1165	<5	0.10	1	17	174	50	5.01	2.43	30	0.36	390	3	1.11	40	960	48	<5	<20	43	0.29	<10	128	<10	7	195
20	C130873	0.3	9.52	20	1460	5	0.08	1	13	126	30	4.54	2.54	30	0.33	331	1	1.25	53	730	32	<5	<20	52	0.31	<10	126	<10	6	136
21	C130874	0.6	8.13	30	1275	5	0.20	2	17	188	36	4.45	2.30	20	0.30	802	14	1.00	51	920	34	<5	<20	46	0.26	<10	215	<10	5	215
22	C130875	0.2	7.86	<5	1055	<5	0.15	<1	11	193	53	3.65	1.99	30	1.50	715	2	0.89	49	750	30	<5	<20	41	0.30	<10	104	<10	5	133
23	C130876	0.4	6.14	<5	910	<5	0.75	<1	6	148	88	2.39	1.72	20	0.56	403	7	0.94	35	830	32	<5	<20	72	0.31	<10	152	<10	6	124
24	C130877	0.5	5.65	10	895	<5	0.04	<1	11	272	63	2.71	1.74	20	0.22	229	3	0.56	49	430	44	<5	<20	30	0.23	<10	108	<10	4	116
25	C130878	0.4	4.81	<5	715	<5	0.84	<1	7	312	52	2.63	1.33	20	0.48	568	<1	0.68	38	620	22	<5	<20	75	0.23	<10	63	<10	5	111

Et #.	Tag #	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K%	La	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Zn
26	C130879	3 7.63	<5 845	5 0.07	<1 15	331	44 4.47	1.88	30 0.27	509	4 1.04	35 750	32 <5	<20 68	0.35	<10 136	<10 6	118									
27	C130880	0.2 5.13	<5 855	<5 0.16	<1 9	271	55 2.93	1.55	20 0.27	528	<1 0.44	64 450	20 <5	<20 29	0.25	<10 78	<10 7	145									
28	C130881	0.4 4.29	<5 745	<5 0.07	<1 7	216	63 2.72	1.35	20 0.20	581	1 0.30	65 270	16 <5	<20 23	0.19	<10 75	<10 5	184									
29	C130882	0.2 6.44	<5 1000	<5 0.48	<1 9	192	92 2.63	1.83	20 0.39	508	1 0.92	59 520	22 <5	<20 50	0.33	<10 112	<10 6	144									
30	C130883	<0.2 1.60	<5 300	<5 0.02	<1 2	325	27 1.29	0.56	<10 0.07	106	2 0.10	18 170	14 5	<20 9	0.06	<10 22	<10 3	43									
31	C130884	<0.2 4.47	<5 830	<5 0.02	<1 4	194	63 2.15	1.45	10 0.19	99	<1 0.28	34 290	16 <5	<20 23	0.17	<10 65	<10 4	77									
32	C130885	0.2 0.22	<5 30	<5 0.03	<1 1	213	7 0.47	0.05	<10 <0.01	69	2 0.06	6 160	6 <5	<20 4	0.01	<10 2	<10 1	12									
33	C130886	0.2 >10	25 1105	5 1.10	<1 18	407	86 5.55	2.86	40 0.28	227	6 0.48	74 6030	32 5	<20 139	0.19	<10 262	<10 19	110									
34	C130887	<0.2 3.37	10 200	<5 0.07	<1 11	210	50 3.62	1.02	20 0.06	220	2 0.33	19 500	16 <5	<20 35	0.11	<10 31	<10 6	49									
35	C130888	0.2 8.85	30 695	5 0.18	<1 14	259	52 5.41	2.29	30 0.16	206	30 0.65	54 1280	34 5	<20 106	0.25	<10 462	<10 8	101									

QC DATA:

Resplit:

1	C130854	2.4 5.60	105 675	5 0.09	3 13	117	98 3.87	1.40	20 0.13	689	28 0.50	50 950	38 10	<20 83	0.09	<10 333	<10 7	210
---	---------	----------	---------	--------	------	-----	---------	------	---------	-----	---------	--------	-------	--------	------	---------	-------	-----

Repeat:

1	C130854	2.3 5.10	95 640	5 0.06	2 13	125	95 3.67	1.38	10 0.13	682	26 0.48	45 870	36 10	<20 80	0.06	<10 305	<10 6	198
10	C130863	<0.2 5.81	30 865	5 0.04	1 3	190	63 3.85	1.86	20 0.24	191	5 0.53	24 550	26 <5	<20 31	0.21	<10 306	<10 4	256
19	C130872	<0.2 8.69	50 1125	<5 0.10	1 17	170	49 4.88	2.58	30 0.35	375	3 1.09	39 940	44 <5	<20 43	0.31	<10 124	<10 7	190

Standard:

STSD-3		0.4 5.78	25 1380	<5 2.49	1 17	61	41 4.16	1.39	40 1.28	2517	6 1.05	31 1660	54 <5	<20 256	0.35	<10 117	<10 32	202
--------	--	----------	---------	---------	------	----	---------	------	---------	------	--------	---------	-------	---------	------	---------	--------	-----

ECO TECH LABORATORY LTD.
 Jutta Jealous
 B.C. Certified Assayer

JJ/sa/
 df/d631
 XLS/07

CERTIFICATE OF ASSAY AK 2007- 631

Mincord Exploration
110-325 Howe Street
Vancouver, BC
V6C 1Z7

20-Jun-07

Attention: Bill Morton

No. of samples received: 35

Sample type: Rock

Project #: Spanish Mountain

Shipment #: SMR-07-01

Samples Submitted by: Johnston

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	C130854	0.10	0.003
2	C130855	<0.03	<0.001
3	C130856	<0.03	<0.001
4	C130857	<0.03	<0.001
5	C130858	<0.03	<0.001
6	C130859	<0.03	<0.001
7	C130860	<0.03	<0.001
8	C130861	<0.03	<0.001
9	C130862	<0.03	<0.001
10	C130863	<0.03	<0.001
11	C130864	<0.03	<0.001
12	C130865	<0.03	<0.001
13	C130866	<0.03	<0.001
14	C130867	<0.03	<0.001
15	C130868	<0.03	<0.001
16	C130869	0.06	0.002
17	C130870	<0.03	<0.001
18	C130871	<0.03	<0.001
19	C130872	<0.03	<0.001
20	C130873	<0.03	<0.001
21	C130874	<0.03	<0.001
22	C130875	<0.03	<0.001
23	C130876	<0.03	<0.001
24	C130877	<0.03	<0.001
25	C130878	<0.03	<0.001

ECO TECH LABORATORY LTD.

Jutta Jealouse

B.C. Certified Assayer

Mincord Exploration AK7-631

20-Jun-07

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	C130879	<0.03	<0.001
27	C130880	<0.03	<0.001
28	C130881	<0.03	<0.001
29	C130882	<0.03	<0.001
30	C130883	<0.03	<0.001
31	C130884	<0.03	<0.001
32	C130885	<0.03	<0.001
33	C130886	<0.03	<0.001
34	C130887	<0.03	<0.001
35	C130888	0.08	0.002

QC DATA:

Resplit:

1	C130854	0.10	0.003
---	---------	------	-------

Repeat:

1	C130854	0.10	0.003
10	C130863	<0.03	<0.001
19	C130872	<0.03	<0.001

Standard:

SI25		1.79	0.052
------	--	------	-------

JJ/sa
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

5-Sep-07
ECO TECH LABORATORY LTD.
 10041 Dallas Drive
KAMLOOPS, B.C.
 V2C 6T4
 Phone: 250-573-5700
 Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AK 2007-0937

Skygold Ventures
 615 - 800 W. Pender Street
Vancouver, BC
 V6B 2V6

No. of samples received: 12
 Sample Type: ROCK
 Project: Spanish Mountain
 Shipment #: **SMC-07-029**
 Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Tag #	Shipno	Certificate	Au(g/t)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
G26051	SMC-07-029	AK2007-0937	0.22	1	8.69	30	985	40	6.81	4	23	129	458	4.89	2.5 <10	2.63	1320	1	0.75	23	900	52 <5	<20	282	0.18 <10	350 <10	14	361				
G26052	SMC-07-029	AK2007-0937	1.56	0.4	0.48	5	730	20	3.78	32	7	219	46	2.59	0.11 <10	1.22	1131	12	0.04	12	390	22	5 <20	218	0.01 <10	17 <10	7	3439				
G26053	SMC-07-029	AK2007-0937	0.65	0.6	0.74	40	100	20	0.25 <1	11	313	27	2.29	0.12 <10	0.06	336	13	0.04	12	220	6	10 <20	24	0.01 <10	8 <10	2	19					
G26054	SMC-07-029	AK2007-0937	0.43 <0.2	1.37	55	250	10	0.01 <1	4	220	9	1.49	0.5 <10	0.04	405	14	0.05	8	60	12	5 <20	9	0.01 <10	47 <10	<1	18						
G26055	SMC-07-029	AK2007-0937	31.5	16.2	0.43	50	50	15	0.01 <1	2	189	5	0.82	0.14 <10	0.02	31	53	0.02	8	90	2984	5 <20	4	0.02 <10	8 <10	<1	9					
G26056	SMC-07-029	AK2007-0937	17.3	28.8	0.02 <5	<5	20	<0.01	33	3	236	97	0.53 <0.01	<10	<0.01	33	17	<0.01	8	20	7256	20 <20	2	<0.01	<10	1	<10	<1	3971			
G26057	SMC-07-029	AK2007-0937	28.8	15.4	0.73	145	70	50	0.19	3	28	364	15	8.54	0.24 <10	0.1	114	36	0.01	53	450	238	15 <20	24	0.02 <10	55 <10	<1	173				
G26058	SMC-07-029	AK2007-0937	1.68	0.8	0.69	35	80	10	0.06 <1	6	434	8	1.42	0.21 <10	0.03	157	7	0.01	18	60	16	10 <20	11	0.02 <10	34 <10	<1	56					
G26059	SMC-07-029	AK2007-0937	1.35	0.2	0.49 <5	60	15	0.58 <1	3	526	80	1.9	0.12 <10	0.07	640	22	0.04	18	330	8	15 <20	27	<0.01	<10	8 <10	3	32					
G26060	SMC-07-029	AK2007-0937	5.2	3.6	0.4 <5	65	<5	0.17	5	3	272	1425	0.84	0.08 <10	0.02	108	15	0.05	12	540	12	10 <20	34	<0.01	<10	5 <10	<1	693				
G26061	SMC-07-029	AK2007-0937	3.23	15.2	0.58 <5	70	30	0.03	5	2	406	2958	1.19	0.09 <10	0.01	177	3	0.05	9	40	772	15 <20	10	<0.01	<10	6 <10	<1	775				
G26062	SMC-07-029	AK2007-0937	0.78 >30	0.22 <5	25	95	0.02	1	2	330	25	0.76	0.02 <10	<0.01	253	30	0.03	9	40	>10000	20 <20	7	<0.01	<10	3 <10	<1	18					
RE-G26051	SMC-07-029	AK2007-0937		1.2	8.76	30	835	45	6.51	4	23	129	477	5.07	2.31	10	2.66	1329	1	0.76	23	920	52	10 <20	284	0.17 <10	353 <10	15	352			
RE-G26060	SMC-07-029	AK2007-0937		3.4	0.35 <5	55	5	0.13	5	2	231	1433	0.81	0.07 <10	<0.01	93	15	0.04	11	530	16	10 <20	29	<0.01	<10	5 <10	1	704				
RE-G26062	SMC-07-029	AK2007-0937																														
RES-G26051	SMC-07-029	AK2007-0937	0.11	1.2	9.06	30	855	30	6.79	5	21	131	504	5.04	2.32 <10	2.68	1355	<1	0.77	24	940	60	5 <20	282	0.18 <10	367 <10	15	373				

ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

10-Aug-07

ECO TECH LABORATORY LTD.
 10041 Dallas Drive
 KAMLOOPS, B.C.
 V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 2007-1077

Skygold Ventures
 615 - 800 W. Pender Street
 Vancouver, BC
 V6B 2V6

Phone: 250-573-5700
 Fax : 250-573-4557

No. of samples received: 42
 Sample Type: Core
 Project: Spanish Mountain
 Shipment #: SMC-07-041
 Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Tag #	Shipno	Certificate	Au (g/t)	Ag	Al%	As	Ba	BI	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
G26063	SMC-07-041	AK2007-1077	1.2	0.8	0.52	35	105	10	0.03	<1	4	215	13	1.16	0.11	<10	0.02	378	1	0.23	12	90	24	<5	<20	18	<0.01	<10	9	<10	3	12
G26064	SMC-07-041	AK2007-1077	0.18	1.8	0.48	5	65	15	0.08	<1	2	243	61	0.93	0.07	<10	0.03	378	1	0.07	8	90	204	<5	<20	12	<0.01	<10	4	<10	1	104
G26065	SMC-07-041	AK2007-1077	0.41	10.2	0.5	<5	75	15	0.07	<1	3	627	21	1.7	0.08	<10	0.03	737	3	0.07	14	210	3500	15	<20	15	<0.01	<10	6	<10	3	32
G26066	SMC-07-041	AK2007-1077	<0.03	0.4	0.64	15	70	10	0.09	<1	2	523	24	0.94	0.05	<10	0.03	394	2	0.03	12	40	38	10	<20	16	<0.01	<10	5	<10	<1	17
G26067	SMC-07-041	AK2007-1077	<0.03	0.2	0.85	10	120	5	0.08	<1	2	299	55	1.15	0.09	<10	0.05	169	2	0.09	8	110	44	<5	<20	11	<0.01	<10	8	<10	5	23
G26068	SMC-07-041	AK2007-1077	<0.03	0.5	5.65	405	120	45	3.14	1	79	1747	103	5.07	0.97	<10	3.89	1081	<1	0.78	863	620	36	35	<20	183	0.04	<10	107	<10	3	161
G26069	SMC-07-041	AK2007-1077	0.04	0.3	5.34	610	155	35	4.29	2	54	1402	30	4.97	1.03	<10	5.29	1306	<1	0.69	549	590	26	30	<20	291	0.05	<10	101	<10	4	165
G26851	SMC-07-041	AK2007-1077	<0.03	<0.2	1.45	<5	55	15	>10	<1	<1	4	9	0.28	0.05	<10	1.7	70	<1	0.02	20	60	4	<5	<20	4836	<0.01	<10	2	<10	1	7
G26070	SMC-07-041	AK2007-1077	<0.03	0.2	1.19	65	185	10	0.22	<1	7	252	123	1.16	0.14	<10	0.07	595	1	0.16	24	190	22	<5	<20	34	0.01	<10	10	<10	1	31
G26071	SMC-07-041	AK2007-1077	<0.03	0.6	1.81	75	800	15	0.14	<1	12	280	133	1.76	0.5	<10	0.08	623	1	0.34	27	170	42	<5	<20	44	0.07	<10	24	<10	2	43
G26072	SMC-07-041	AK2007-1077	0.03	<0.2	0.99	<5	60	<5	0.07	<1	1	236	9	0.68	0.11	<10	0.03	125	1	0.08	7	70	6	<5	<20	19	<0.01	<10	3	<10	<1	30
G26073	SMC-07-041	AK2007-1077	0.03	0.3	1.64	100	450	20	0.11	<1	6	331	63	2.49	0.33	<10	0.09	1238	<1	0.55	18	280	78	5	<20	40	0.04	<10	56	<10	4	27
G26074	SMC-07-041	AK2007-1077	0.53	0.4	3.11	25	150	10	0.06	<1	6	131	63	1.79	0.18	<10	0.29	790	<1	1.32	18	160	18	<5	<20	51	0.1	<10	42	<10	2	46
G26075	SMC-07-041	AK2007-1077	0.4	13	4.82	50	510	30	2.6	65	25	272	2945	4.34	0.6	<10	1.39	1131	1	1.19	33	780	292	<5	<20	242	0.32	<10	133	<10	8	6753
G26076	SMC-07-041	AK2007-1077	<0.03	0.5	5.15	60	565	25	1.83	8	19	118	90	3.4	0.66	<10	1.38	1055	<1	1.17	33	640	26	<5	<20	178	0.29	<10	116	<10	7	1563
G26077	SMC-07-041	AK2007-1077	0.26	2.4	1.59	40	185	15	0.09	<1	8	598	46	2.12	0.38	<10	0.05	162	2	0.17	18	190	10	10	<20	25	0.01	<10	15	<10	<1	25
G26078	SMC-07-041	AK2007-1077	<0.03	<0.2	1.65	<5	145	<5	0.67	<1	1	265	12	0.79	0.27	<10	0.17	464	1	0.3	7	400	8	<5	<20	56	0.13	<10	19	<10	2	14
G26079	SMC-07-041	AK2007-1077	0.28	0.8	6.43	40	975	20	1.9	<1	6	91	138	1.76	1.78	<10	0.47	545	<1	3.29	26	1320	22	<5	<20	238	0.11	<10	127	<10	3	36

Tag #	Shipno	Certificate	Au (g/t)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
G26852	SMC-07-041	AK2007-1077	2	4.6	4.62	175	935	40	0.49	2	13	42	567	5.16	2.36	10	1.69	382	8	0.22	22	480	98	50 <20	62	0.28 <10	55 <10	11	648			
G26080	SMC-07-041	AK2007-1077	1.62	1	1.22	45	80	15	0.17 <1	4	346	24	1.33	0.11 <10	0.05	491	2	0.04	21	240	396	5 <20	26 <0.01 <10	5 <10	3	90						
G26081	SMC-07-041	AK2007-1077	0.73 <0.2		0.88	30	120	5	0.07 <1	6	294	10	1.07	0.22 <10	0.02	452	2	0.1	17	260	12 <5	<20	44	0.02 <10	17 <10	1	28					
G26082	SMC-07-041	AK2007-1077	10.2 >30		0.82	210	65	25	0.11	2	5	426	68	2.34	0.09 <10	0.04	505	2	0.05	25	140 >10000	35 <20	29	0.01 <10	4 <10	2	297					
G26083	SMC-07-041	AK2007-1077	0.03	0.2	0.37	10	70	10	0.04 <1	3	487	15	0.97	0.08 <10	0.01	364	2	0.03	18	140	100	5 <20	16 <0.01 <10	5 <10	<1	32						
G26084	SMC-07-041	AK2007-1077	1.32 >30		0.14	45	50	15	0.01 <1	1	356	5674	2.24	0.03 <10	<0.01	70	2	0.02	6	110	68	270 <20	5 <0.01 <10	4 <10	<1	74						
G26085	SMC-07-041	AK2007-1077	0.11	0.2	1.47	15	155	20	0.3 <1	5	586	29	1.67	0.34 <10	0.09	445	2	0.36	23	510	12	10 <20	62	0.02 <10	20 <10	2	25					
G26086	SMC-07-041	AK2007-1077	1.98	9	0.19	15	30	5	0.02	1 <1	238	1778	0.85	0.04 <10	<0.01	41	1	0.03	6	70	12	5 <20	5 <0.01 <10	4 <10	<1	151						
G26087	SMC-07-041	AK2007-1077	1.6	11	1.11	15	60	30	0.14 <1	3	611	16	1.17	0.09 <10	0.04	196	2	0.07	17	380	5430	15 <20	24 <0.01 <10	4 <10	<1	66						
G26088	SMC-07-041	AK2007-1077	15.6	4.2	6.35	140	125	30	0.05	1	14	550	19	4.7	2.57	20	0.25	107	78	0.09	74	410	98	10 <20	23	0.15 <10	493 <10	7	196			
G26089	SMC-07-041	AK2007-1077	212 >30		0.21	10	30 <5		0.06 <1	3	250	15	0.87	0.09 <10	<0.01	39	3 <0.01	10	240	22 <5	<20	8 <0.01 <10	5 <10	<1	48							
G26853	SMC-07-041	AK2007-1077	<0.03	<0.2	0.87 <5	40	10 >10	<1	<1	3	14	0.13	0.03 <10	1.8	52 <1	<0.01	19	60	4 <5	<20	4943 <0.01 <10	2 <10	<1	5								
G26090	SMC-07-041	AK2007-1077	65.7 >30		0.05	5 <5	45	0.63	87	4	177	123	0.81 <0.01	<10	0.02	34	3 <0.01	10	20 >10000	35 <20	83 <0.01 <10	1 <10	<1	9149								
G26091	SMC-07-041	AK2007-1077	426 >30		0.08	110	15	265	0.02	3	2	364	83	1.27	0.02 <10	<0.01	46	3 <0.01	9	30 >10000	45 <20	13 <0.01 <10	2 <10	<1	107							
G26092	SMC-07-041	AK2007-1077	12.2	19.1	2.14	10	160	20	1.16	11	4	293	1802	1.6	0.58 <10	0.37	471	2	0.67	8	220	322	5 <20	92	0.06 <10	39 <10	3	1184				
G26093	SMC-07-041	AK2007-1077	0.07	14.6	0.48	10	175	10	0.09	1	5	487	4393	1.33	0.2 <10	0.05	315	3	0.02	14	70	34	10 <20	11	0.01 <10	15 <10	<1	140				
G26094	SMC-07-041	AK2007-1077	18.3	13.9	0.56	115	70	10	0.03	14	3	268	32	1.26	0.22 <10	0.02	39	7	0.01	10	300	3502	5 <20	12	0.01 <10	10 <10	1	1574				
G26095	SMC-07-041	AK2007-1077	16.8	5.5	0.94	115	150	15	0.03	4	9	372	23	1.78	0.35 <10	0.04	66	5	0.02	33	80	50	10 <20	7	0.02 <10	17 <10	1	390				
G26096	SMC-07-041	AK2007-1077	21.3 >30		0.04	10	5	195	0.01	17	2	268	524	0.56 <0.01	<10	<0.01	76	19 <0.01	8	20 >10000	180 <20	9 <0.01 <10	2 <10	<1	656							
G26097	SMC-07-041	AK2007-1077	0.53	0.8	0.35 <5	70	15	0.08	3	2	297	54	1.67	0.09 <10	0.02	514	5	0.03	11	280	132	5 <20	10 <0.01 <10	6 <10	4	356						
G26098	SMC-07-041	AK2007-1077	0.4	1.8	0.2	5	50	5	0.29	11	4	519	31	1.12	0.07 <10	0.05	239	4 <0.01	15	860	188	15 <20	31 <0.01 <10	12 <10	3	972						
G26099	SMC-07-041	AK2007-1077	<0.03	0.3	0.68 <5	40 <5		0.04 <1	<1	220	25	0.44	0.05 <10	0.02	88	1	0.01	6	20	16 <5	<20	7 <0.01 <10	4 <10	<1	6							
G26854	SMC-07-041	AK2007-1077	0.41	0.9	5.75	110	220	15	0.29 <1	8	24	42	3.67	4.57 <10	0.37	171	4	0.07	14	440	18	40 <20	40	0.36 <10	71 <10	9	49					
G26100	SMC-07-041	AK2007-1077	<0.03	<0.2	0.1 <5	25	15 <0.01	<1	1	376	7	0.62	0.03 <10	<0.01	111	2	0.01	10	30	12	5 <20	3 <0.01 <10	6 <10	<1	3							
RE-G26063	SMC-07-041	AK2007-1077		0.8	1.05	35	140	10	0.03 <1	4	221	13	1.18	0.14 <10	0.07	393	1	0.24	12	100	26	5 <20	17 <0.01 <10	9 <10	2	13						
RE-G26071	SMC-07-041	AK2007-1077		0.7	1.68	75	835	10	0.13 <1	12	259	133	1.64	0.47 <10	0.07	592	1	0.35	26	160	42 <5	<20	44	0.07 <10	24 <10	2	42					
RE-G26095	SMC-07-041	AK2007-1077		4	0.85	105	145	15	0.04	3	9	385	33	1.73	0.34 <10	0.04	75	5	0.02	32	80	48	5 <20	8	0.02 <10	16 <10	1	381				
RES-G26063	SMC-07-041	AK2007-1077	0.43	0.9	0.68	30	130	15	0.04 <1	4	213	21	1.2	0.11 <10	0.02	376	2	0.21	15	110	24	5 <20	20	0.01 <10	10 <10	2	18					
RES-G26095	SMC-07-041	AK2007-1077	11.9	2.6	0.67	110	130	5	0.04	5	9	378	22	1.7	0.3 <10	0.04	57	4	0.02	31	70	58	5 <20	7	0.02 <10	15 <10	2	403				

ECO TECH LABORATORY LTD.

Jutta Jealous

B.C. Certified Assayer

13-Sep-07

ECO TECH LABORATORY LTD.
 10041 Dallas Drive
KAMLOOPS, B.C.
 V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 2007-1023

Skygold Ventures
 615 - 800 W. Pender Street
Vancouver, BC
 V6B 2V6

Phone: 250-573-5700
 Fax : 250-573-4557

No. of samples received: 49
 Sample Type: Rock
Project: Spanish Mountain
Shipment #: SMC-07-042
 Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Tag #	Shipno	Certificate	Au(g/t)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
G26201	SMC-07-042	AK2007-1023	0.05	0.6	1.15	5	75 <5		0.22 <1	1	239	6	0.64	0.17 <10	0.06	198	5	0.31	8	140	8 <5	<20	31	0.02 <10	11 <10	<1					13	
G26202	SMC-07-042	AK2007-1023	0.08	0.2	1.72	5	60 <5		0.16 <1	2	189	8	0.57	0.13 <10	0.05	233	1	1.15	8	160	8 <5	<20	35	0.05 <10	11 <10	1					12	
G26203	SMC-07-042	AK2007-1023	7.92	0.8	0.82 <5	50 <5			0.22 <1	2	588	8	1.02	0.08 <10	0.05	339	12	0.23	12	110	8	5 <20	28	0.01 <10	7 <10	<1					16	
G26204	SMC-07-042	AK2007-1023	0.03	0.4	1.63	25	110 <5	>10	<1	5	322	7	4.89	0.2 <10	2.83	3036	1	0.15	25	90	12 <5	<20	607 <0.01	<10	24 <10	10					52	
G26205	SMC-07-042	AK2007-1023	232 >30	1.86	25	245	320	1.41	297	5	410	2940	2	0.43 <10	0.38	462	6	0.2	31	250 >10000	15 <20	135	0.02 <10	17 <10	2	>10000						
G26206	SMC-07-042	AK2007-1023	0.14	1	5.13	770	520	10	9.29	10	90	1196	80	5.69	1.13 <10	3.05	2526 <1	0.43	1283	570	386	20 <20	422	0.04 <10	57 <10	5					672	
G26207	SMC-07-042	AK2007-1023	0.32	1.2	2.56	670	335	10	9.14	5	132	3584	69	4.11	0.7 <10	3.62	2228	8	0.1	1917	110	132	50 <20	366	0.01 <10	47 <10	2					470
G26208	SMC-07-042	AK2007-1023	17.8	11.4	0.82	25	35	10	0.27	17	4	399	20	1.01	0.07 <10	0.08	112	10	0.03	26	90	2072	10 <20	35 <0.01	<10	3 <10	<1					2026
G26209	SMC-07-042	AK2007-1023	0.07	1.2	1.17	145	215	10	0.18	2	17	399	22	3.14	0.29 <10	0.07	1520	7	0.04	110	140	88	15 <20	21	0.02 <10	11 <10	2					243
G26210	SMC-07-042	AK2007-1023	1.38	0.6	1.04	30	50 <5		0.25 <1	6	442	19	1.91	0.1 <10	0.08	222	10	0.04	29	150	66	5 <20	27	0.01 <10	6 <10	<1					76	
G26211	SMC-07-042	AK2007-1023	0.05	0.6	0.8	30	60 <5		0.16 <1	6	472	20	1.95	0.1 <10	0.08	218	5	0.03	29	150	58	10 <20	23 <0.01	<10	6 <10	<1					75	
G26212	SMC-07-042	AK2007-1023	484 >30	1.13	5	125	5	0.68	2	3	650	14	2.6	0.15 <10	0.1	1230	4	0.03	16	100	390	10 <20	30	0.01 <10	8 <10	7					207	
G26213	SMC-07-042	AK2007-1023	1.69	20.1	4.72 <5	375	25	1.35	15	3	343	19	3.07	1.31 <10	0.22	1376	2	0.98	11	490	4462	10 <20	83	0.12 <10	85 <10	12					1681	
G26214	SMC-07-042	AK2007-1023	33.9 >30	0.95	5	45	95	0.65	23	2	468	36	1.61	0.06 <10	0.09	712	3	0.03	10	60 >10000	20 <20	42 <0.01	<10	4 <10	3					2449		
G26215	SMC-07-042	AK2007-1023	16.6	10.8	0.9	15	70	10	0.26	5	2	452	20	0.91	0.08 <10	0.05	200	13	0.06	11	180	1592	5 <20	35 <0.01	<10	5 <10	<1					637
G26216	SMC-07-042	AK2007-1023	32.5 >30	0.15	35	125	30	0.05	28	6	247	120	1.5	0.01 <10	0.01	90	10	0.03	16	40	6518	10 <20	8 <0.01	<10	2 <10	<1					3846	
G26217	SMC-07-042	AK2007-1023	29.6 >30	1.03	45	205	40	0.23	27	5	349	124	1.66	0.1 <10	0.04	153	2	0.07	17	90	7538	10 <20	37 <0.01	<10	3 <10	<1					3701	
G26218	SMC-07-042	AK2007-1023	11.1 >30	1.03 <5	50	80	2.82	21	2	723	36	2.61	0.06 <10	0.26	1145	14	0.04	14	40	7400	25 <20	100 <0.01	<10	5 <10	8					4006		

Tag #	Shipno	Certificate	Au(g/t)	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
G26219	SMC-07-042	AK2007-1023	0.26 >30	1.27	75	150	115	0.27	51	5	452	255	2.11	0.19 <10	0.06	237	3	0.1	11	230	>10000	30 <20	47	0.01 <10	8 <10	<1	5109					
G26220	SMC-07-042	AK2007-1023	1.8 >30	0.86 <5	65	55	1.17	40	2	682	45	2.32	0.08 <10	0.16	1021	15	0.05	12	70	8740	20 <20	49	<0.01 <10	5 <10	6	4099						
G26221	SMC-07-042	AK2007-1023	<0.03	13.2	1.33 <5	115	50	0.28	1	3	413	21	1.02	0.14 <10	0.05	196	15	0.11	11	110	1684	5 <20	31	<0.01 <10	6 <10	<1	137					
G26222	SMC-07-042	AK2007-1023	<0.03	7.9	1.17 <5	85	30	0.34 <1	4	482	28	1.17	0.13 <10	0.06	206	5	0.05	14	80	952	10 <20	32	<0.01 <10	7 <10	<1	57						
G26223	SMC-07-042	AK2007-1023	0.08	0.4	1.24	30	100 <5	0.41 <1	9	462	12	1.72	0.29 <10	0.08	169	3	0.06	34	150	62	5 <20	32	0.03 <10	12 <10	1	40						
G26224	SMC-07-042	AK2007-1023	152 >30	3.7	50	165 <5	3.17	93	42	329	>10000	9.78	0.36 <10	1.61	898	4	0.88	10	710	400	5 <20	165	0.16 <10	87 <10	6	>10000						
G26225	SMC-07-042	AK2007-1023	7.71	4.2	1.36	20	50 <5	1.29	3	6	401	1212	2.15	0.1 <10	0.22	483	2	0.44	24	220	28	5 <20	64	0.02 <10	8 <10	5	448					
G26226	SMC-07-042	AK2007-1023	1.98	2.8	1.78	20	130 <5	0.37 <1	4	635	104	1.95	0.33 <10	0.09	628	3	0.72	25	800	20	10 <20	68	0.03 <10	19 <10	3	108						
G26227	SMC-07-042	AK2007-1023	9	3.9	1.13	130	55	5	0.34 <1	6	322	35	2.65	0.11 <10	0.13	125	3	0.05	13	240	234 <5	<20	33	<0.01 <10	4 <10	1	20					
G26228	SMC-07-042	AK2007-1023	0.09	3.6	1.01	120	45	5	0.31	1	7	532	22	3	0.1 <10	0.1	110	15	0.05	17	220	356	5 <20	33	<0.01 <10	6 <10	<1	73				
G26229	SMC-07-042	AK2007-1023	<0.03	<0.2	0.98 <5	50 <5	0.25 <1	<1	463	10	0.7	0.09 <10	0.1	92	13	0.05	9	40	20	5 <20	30	<0.01 <10	2 <10	<1	17							
G26230	SMC-07-042	AK2007-1023	<0.03	<0.2	1.11 <5	55 <5	0.25 <1	2	527	16	0.94	0.11 <10	0.1	111	12	0.08	13	90	22	5 <20	34	0.01 <10	9 <10	<1	22							
G26231	SMC-07-042	AK2007-1023	<0.03	0.4	0.75 <5	30	5	0.24 <1	<1	240	7	0.45	0.02 <10	0.05	89	2	0.04	6	30	8 <5	<20	52	<0.01 <10	1 <10	2	13						
G26232	SMC-07-042	AK2007-1023	0.38	0.6	5.4	65	880 <5	0.35	1	16	244	32	3.65	1.55	20	0.3	929	13	0.89	35	1090	68 <5	<20	49	0.23 <10	175 <10	5	171				
G26233	SMC-07-042	AK2007-1023	1.78 >30	0.77	5	65	165	0.18	2	4	429	25	1.2	0.09 <10	0.08	108	14	0.05	19	60	>10000	10 <20	20	0.01 <10	15 <10	<1	33					
G26234	SMC-07-042	AK2007-1023	<0.03	0.4	1.05 <5	60 <5	0.24 <1	10	501	40	1.36	0.1 <10	0.08	111	3	0.07	22	110	152	5 <20	28	0.01 <10	4 <10	<1	17							
G26235	SMC-07-042	AK2007-1023	0.03	0.2	1.28	5	105 <5	0.29 <1	2	448	18	0.87	0.12 <10	0.07	163	11	0.06	12	170	78	50 <20	37	<0.01 <10	4 <10	<1	39						
G26236	SMC-07-042	AK2007-1023	<0.03	0.4	0.75	20	95 <5	0.16 <1	<1	165	17	0.58	0.06 <10	0.08	83	2	0.03	6	80	18 <5	<20	30	<0.01 <10	3 <10	<1	36						
G26237	SMC-07-042	AK2007-1023	<0.03	0.6	1.44	55	160 <5	0.23 <1	16	519	107	1.76	0.36 <10	0.06	595	3	0.29	46	510	48	5 <20	42	0.03 <10	49 <10	2	41						
G26238	SMC-07-042	AK2007-1023	0.05	1.6	4.48	85	205	10	0.29 <1	20	300	80	9.22	1.43	20	0.25	57	72	0.61	99	490	84	10 <20	40	0.08 <10	249 <10	5	54				
G26239	SMC-07-042	AK2007-1023	<0.03	0.4	2.3 <5	400 <5	1 <1	4	410	91	2.06	0.43 <10	0.35	289	9	0.46	11	460	12 <5	<20	161	0.14 <10	56 <10	8	24							
G26240	SMC-07-042	AK2007-1023	<0.03	<0.2	1.2 <5	60 <5	0.24 <1	<1	247	8	0.53	0.08 <10	0.05	147	6	0.07	6	60	8 <5	<20	33	<0.01 <10	3 <10	<1	8							
G26241	SMC-07-042	AK2007-1023	0.21	3	4.85	20	280 <5	0.06 <1	9	159	27	3.57	1.54	20	0.23	56	35	0.31	34	250	52	5 <20	29	0.1 <10	149 <10	7	108					
G26242	SMC-07-042	AK2007-1023	<0.03	0.2	0.99 <5	65	5	0.21 <1	1	548	12	0.8	0.09 <10	0.05	152	15	0.04	12	40	8	5 <20	30	<0.01 <10	8 <10	<1	15						
G26243	SMC-07-042	AK2007-1023	<0.03	0.3	1.3	75	95	10	0.22	1	15	426	17	5.66	0.11 <10	0.09	372	6	0.23	100	590	12	5 <20	89	0.01 <10	48 <10	1	90				
G26244	SMC-07-042	AK2007-1023	0.41	10.1	5.95	70	460	15	0.2	2	20	199	99	8.94	2.09	10	0.31	101	82	0.69	101	780	194	30 <20	39	0.1 <10	351 <10	5	227			
G26245	SMC-07-042	AK2007-1023	0.45	14.5	6.17	100	350	10	0.2	2	20	199	91	9.49	2.11	20	0.35	112	95	0.61	94	600	230	30 <20	46	0.11 <10	354 <10	5	209			
G26246	SMC-07-042	AK2007-1023	<0.03	1.5	1.02	15	65 <5	0.7 <1	3	478	15	1.01	0.15	20	0.06	108	15	0.12	20	1710	12	5 <20	53	0.02 <10	21 <10	5	29					
G26247	SMC-07-042	AK2007-1023	<0.03	0.2	7.01	125	300	5	4.54	2	43	595	62	7.18	0.95 <10	3.9	1146	4	1.32	228	1200	52	10 <20	327	0.08 <10	242 <10	7	210				
G26248	SMC-07-042	AK2007-1023	<0.03	2	0.24	10	30 <5	0.11 <1	2	258	10	1.01	0.04 <10	0.07	654	2	0.04	28	200	8 <5	<20	12	<0.01 <10	11 <10	2	17						
G26249	SMC-07-042	AK2007-1023	<0.03	<0.2	1.76 <5	75 <5	>10	<1	<1	10	4	0.44	0.08 <10	1.58	141 <1	0.06	33	110	10 <5	<20	4983	0.02 <10	8 <10	2	8							
RE-G26201	SMC-07-042	AK2007-1023	0.4	1.12	5	65 <5	0.2 <1	1	261	6	0.58	0.1 <10	0.05	180	5	0.3	9	140	10 <5	<20	29	0.02 <10	11 <10	<1	13							
RE-G26210	SMC-07-042	AK2007-1023	0.7	0.99	25	50	5	0.26 <1	6	440	18	1.98	0.13 <10	0.08	229	11	0.04	28	150	64	10 <20	29	0.01 <10	7 <10	<1	74						

Tag #	Shipno	Certificate	Au(g/t)	Ag	Al%	As	Ba	Bi	Ce%	Cd	Co	Cr	Cu	Fe%	K%	La	Mg%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
RE-G26219	SMC-07-042	AK2007-1023	>30	1.42	75	160	115	0.28	52	6	446	259	2.16	0.18	<10	0.07	245	3	0.1	11	240	>10000	30	<20	48	0.01	<10	9	<10	<1	5745	
RE-G26236	SMC-07-042	AK2007-1023	0.4	0.77	25	85	<5	0.2	<1	<1	154	18	0.58	0.07	<10	0.07	76	2	0.04	8	80	22	<5	<20	29	<0.01	<10	6	<10	<1	40	
RE-G26245	SMC-07-042	AK2007-1023	12.6	5.97	100	355	15	0.23	2	19	185	84	9.2	2.07	10	0.33	109	92	0.55	91	560	226	30	<20	42	0.09	<10	342	<10	6	208	
RES-G26201	SMC-07-042	AK2007-1023	0.3	1.19	<5	70	5	0.24	<1	2	244	6	0.86	0.14	<10	0.07	207	5	0.3	8	140	10	5	<20	34	0.02	<10	13	<10	1	18	
RES-G26236	SMC-07-042	AK2007-1023	0.4	0.79	25	95	<5	0.18	<1	2	161	16	0.57	0.08	<10	0.06	88	4	0.03	8	90	18	5	<20	30	<0.01	<10	3	<10	<1	37	

ECO TECH LABORATORY LTD.

Jutta Jealous

B.C. Certified Assayer

10-Aug-07

ECO TECH LABORATORY LTD.
 10041 Dallas Drive
KAMLOOPS, B.C.
 V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK07-1042

Skygold Ventures
 615 - 800 W. Pender Street
Vancouver, BC
 V6B 2V6

Phone: 250-573-5700
 Fax : 250-573-4557

No. of samples received: 44
 Sample Type: Core
 Project: Spanish Mountain
 Shipment #: SMC-07-46
 Samples submitted by: Tasha Gainer

Values in ppm unless otherwise reported

Tag #	Shipno	Certificate	Au (g/t)	Ag	Al	As	Ba	Bi	Ca	Cd	Co	Cr	Cu	Fe	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	Sb	Sn	Sr	Ti	U	V	W	Y	Zn
G26250	SMC-07-46	AK07-1042SKY	0.42	0.9	5.01	105	225	15	0.2	<1	8	25	36	2.73	2.99	10	0.28	173	4	0.07	14	450	18	45 <20	43	0.39	<10	74	<10	12	49	
G26251	SMC-07-46	AK07-1042SKY	0.03	8.2	0.19	10	30	10	0.02	<1	2	418	8	0.84	0.04	<10	0.01	214	3	0.01	15	30	2136	10 <20	3	<0.01	<10	4	<10	<1	8	
G26252	SMC-07-46	AK07-1042SKY	0.41	>30	0.63	<5	50	65	0.09	13	2	580	17	0.75	0.02	<10	0.04	106	3	0.01	11	30	>10000	35 <20	17	<0.01	<10	2	<10	<1	921	
G26253	SMC-07-46	AK07-1042SKY	<0.03	<0.2	1.42	<5	50	<5	>10	<1	<1	3	<1	0.15	0.03	<10	1.69	69	<1	0.02	18	50	58	<5	<20	4814	<0.01	<10	1	<10	1	6
G26254	SMC-07-46	AK07-1042SKY	<0.03	1.2	0.06	<5	10	10	0.1	<1	2	628	61	0.98	<0.01	<10	<0.01	219	4	<0.01	15	70	66	15 <20	10	<0.01	<10	4	<10	<1	9	
G26255	SMC-07-46	AK07-1042SKY	<0.03	0.4	0.55	5	60	10	0.1	<1	2	356	5	1.08	0.02	<10	0.03	625	2	0.02	14	60	18	5 <20	24	<0.01	<10	3	<10	3	13	
G26256	SMC-07-46	AK07-1042SKY	4.24	8.7	0.24	25	30	15	0.07	50	4	442	19	1.26	0.08	<10	0.02	94	5	<0.01	22	140	3288	15 <20	8	<0.01	<10	16	<10	<1	5019	
G26257	SMC-07-46	AK07-1042SKY	<0.03	0.3	0.18	5	25	10	0.1	<1	3	232	6	0.92	0.04	<10	0.03	215	2	0.02	19	50	10	<5	<20	12	<0.01	<10	8	<10	2	50
G26258	SMC-07-46	AK07-1042SKY	<0.03	0.2	0.14	<5	5	5	0.03	<1	1	218	8	0.59	<0.01	<10	<0.01	56	2	0.09	7	130	18	<5	<20	3	<0.01	<10	2	<10	1	15
G26259	SMC-07-46	AK07-1042SKY	3.96	4.2	0.91	30	80	5	0.09	6	2	249	8	1.14	0.05	<10	0.02	95	2	0.03	8	60	1444	10 <20	18	<0.01	<10	2	<10	<1	420	
G26260	SMC-07-46	AK07-1042SKY	6.62	6.2	0.58	15	65	10	0.13	5	4	470	8	1.25	0.17	<10	0.04	251	5	0.04	17	110	720	10 <20	9	0.02	<10	7	<10	2	535	
G26261	SMC-07-46	AK07-1042SKY	0.31	<0.2	0.03	<5	30	<5	0.03	<1	1	199	5	0.52	<0.01	<10	<0.01	631	2	<0.01	8	150	4	<5	<20	7	<0.01	<10	3	<10	<1	6
G26262	SMC-07-46	AK07-1042SKY	3.62	12.9	0.38	25	45	10	0.17	8	5	509	13	1.24	0.11	<10	0.06	122	5	0.01	27	110	3846	15 <20	14	<0.01	<10	28	<10	1	875	
G26263	SMC-07-46	AK07-1042SKY	2.01	4.9	4.76	115	355	30	0.45	2	12	35	623	5.08	2.42	10	1.68	392	8	0.21	21	470	106	55 <20	62	0.29	<10	58	<10	12	653	

Tag #	Shipno	Certificate	Au (g/t)	Ag	Al	As	Ba	Bl	Cs	Cd	Co	Cr	Cu	Fe	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	Sb	Sn	Sr	Tl	U	V	W	Y	Zn
G26264	SMC-07-46	AK07-10425KY	6.75	4.4	0.11	5	15 <5		0.01 <1	2	204	5	0.71	0.04 <10	<0.01	183	2 <0.01	9	80	848	5 <20	1 <0.01	<10	3 <10	1	26						
G26265	SMC-07-46	AK07-10425KY	11.9	22.8	0.02	20 <5	15	0.22	11	3	381	12	1.39 <0.01	<10	0.08	119	3 <0.01	13	50	4572	15 <20	13 <0.01	<10	2 <10	<1	1149						
G26266	SMC-07-46	AK07-10425KY	0.15	0.4	0.37	15	30	5	0.1 <1	4	242	73	1.05	0.04 <10	0.05	76	2	0.02	22	60	12	5 <20	10 <0.01	<10	6 <10	<1	21					
G26267	SMC-07-46	AK07-10425KY	<0.03	0.2	0.13	10	25 <5		0.01 <1	1	212	5	0.63	0.03 <10	<0.01	250	3	0.01	10	50	8 <5	<20	4 <0.01	<10	5 <10	<1	7					
G26268	SMC-07-46	AK07-10425KY	0.29 >30		0.05	125	5	310	0.01	7	14	293	158	1.51 <0.01	<10	0.01	151	3 <0.01	51	80 >10000	60 <20	3 <0.01	<10	4 <10	<1	42						
G26269	SMC-07-46	AK07-10425KY	0.56	20.1	0.74	15	55	30	2.3	1	2	647	78	1.71	0.06 <10	1.12	651	4	0.02	20	240	8904	20 <20	202 <0.01	<10	7 <10	4	75				
G26270	SMC-07-46	AK07-10425KY	<0.03	0.6	0.93 <5		75 <5		0.16 <1	2	274	8	0.66	0.09 <10	0.03	233	2	0.02	7	40	94 <5	<20	16 <0.01	<10	7 <10	<1	8					
G26271	SMC-07-46	AK07-10425KY	0.29 <0.2		0.88	5	85	5	0.14 <1	2	584	11	1.11	0.16 <10	0.04	141	2	0.05	12	310	24	10 <20	25	0.02 <10	10 <10	1	10					
G26272	SMC-07-46	AK07-10425KY	0.03 <0.2		0.97	10	55 <5		0.2 <1	2	276	5	0.63	0.24 <10	0.04	100	3	0.03	8	610	12	5 <20	36 <0.01	<10	3 <10	1	6					
G26273	SMC-07-46	AK07-10425KY	0.28	5.5	1.79	15	265	20	0.05	1	3	333	485	1.31	0.68 <10	0.07	237	6	0.16	13	220	796	10 <20	13	0.07 <10	37 <10	3	217				
G26274	SMC-07-46	AK07-10425KY	4.6	18.4	1.97	15	285	30	0.06	2	2	318	89	1.16	0.63 <10	0.08	203	3	0.16	14	150	5046	10 <20	15	0.08 <10	38 <10	3	187				
G26275	SMC-07-46	AK07-10425KY	0.27	2.8	1.25	10	140	10	0.06 <1	2	310	320	0.75	0.35 <10	0.04	157	3	0.14	9	160	153	10 <20	14	0.04 <10	24 <10	2	70					
G26276	SMC-07-46	AK07-10425KY	<0.03	<0.2	0.74 <5		30	5 >10	<1	<1	6	2	0.11	0.02 <10	1.6	51 <1		0.01	16	40	3 <5	<20	4987 <0.01	<10	1 <10	<1	2					
G26277	SMC-07-46	AK07-10425KY	0.08	3	0.5 <5		35	20	0.97	2	2	341	9	0.87	0.14 <10	0.06	180	2	0.01	11	80	471	10 <20	84 <0.01	<10	4 <10	2	170				
G26278	SMC-07-46	AK07-10425KY	<0.03	0.6	0.77	10	65	15	0.05 <1	4	589	14	1.57	0.23 <10	0.02	209	3	0.03	17	60	78	15 <20	11	0.01 <10	7 <10	1	87					
G26279	SMC-07-46	AK07-10425KY	0.53	15.5	0.91	10	95	45	0.06	1	3	331	13	1.33	0.16 <10	0.03	187	2	0.04	12	110	2217	10 <20	13	0.01 <10	8 <10	2	142				
G26280	SMC-07-46	AK07-10425KY	0.26	10.4	0.75	10	55	35	0.35	10	4	615	12	1.29	0.1 <10	0.13	218	3	0.02	16	50	1566	15 <20	38 <0.01	<10	5 <10	2	740				
G26281	SMC-07-46	AK07-10425KY	8.75	6.6	0.64	15	105	15	0.1	14	2	303	351	1.32	0.32 <10	0.04	155	3	0.01	12	140	1146	10 <20	16	0.02 <10	10 <10	1	1042				
G26282	SMC-07-46	AK07-10425KY	0.2	8	1 <5		115	25	0.46	20	4	580	21	1.2	0.34 <10	0.19	262	4	0.02	13	120	2226	15 <20	50	0.02 <10	11 <10	3	1378				
G26283	SMC-07-46	AK07-10425KY	0.43	0.9	5.32	100	290	5	0.21 <1	9	25	34	3.03	3.45	10	0.37	174	4	0.07	14	450	20	45 <20	43	0.39 <10	73 <10	11	55				
G26284	SMC-07-46	AK07-10425KY	4.69	3.8	0.39	30	25	10	0.11	3	3	276	17	1.84	0.12 <10	0.04	72	2	0.01	33	30	4071	10 <20	17 <0.01	<10	2 <10	<1	201				
G26285	SMC-07-46	AK07-10425KY	32.4 >30		0.99	60	90	15	0.1	15	2	495	623	1.16	0.17 <10	0.01	106	5	0.02	10	170 >10000	455 <20	26	0.01 <10	8 <10	<1	1073					
G26286	SMC-07-46	AK07-10425KY	22.7 >30		1	30	120	15	0.06	27	2	571	845	1.64	0.13 <10	0.02	163	5	0.01	15	120 >10000	170 <20	21	0.02 <10	15 <10	1	2423					
G26287	SMC-07-46	AK07-10425KY	1.22 >30		0.93	35	115	5	0.38	12	1	315	2820	0.68	0.16 <10	0.16	199	2	0.01	6	160	72	415 <20	57	0.02 <10	9 <10	1	412				
G26288	SMC-07-46	AK07-10425KY	1.49 >30		0.66	40	75	15	0.04	3	1	563	256	0.92	0.21 <10	0.02	87	14	0.01	10	90 >10000	315 <20	18	0.02 <10	16 <10	<1	57					
G26289	SMC-07-46	AK07-10425KY	0.21	12.8	0.26	30	20 <5		0.07 <1	1	244	56	0.84	0.25 <10	0.01	42	2 <0.01	8	270	402	125 <20	13 <0.01	<10	5 <10	1	18						
G26290	SMC-07-46	AK07-10425KY	0.67 >30		0.43	25	55	20	0.04	27	1	336	689	0.66	0.12 <10	0.02	71	6	0.01	8	110 >10000	440 <20	18 <0.01	<10	10 <10	<1	2205					
G26291	SMC-07-46	AK07-10425KY	0.24	8.3	0.24 <5		35	10	0.06	20	<1	265	22	0.45	0.08 <10	0.01	74	2 <0.01	7	240	2786	10 <20	12 <0.01	<10	5 <10	<1	1723					
G26292	SMC-07-46	AK07-10425KY	2.74 >30		0.06	200	15	15	0.11	65	2	690 >10000	1.85	0.03 <10	0.04	110	5 <0.01	16	100 >10000	7350 <20	19 <0.01	<10	3 <10	<1	3188							
G26293	SMC-07-46	AK07-10425KY	0.04	2.2	0.53	15	75	10	0.02 <1	2	313	26	1.36	0.21 <10	0.08	122	2	0.02	10	70	414	25 <20	5	0.02 <10	13 <10	<1	72					
REG26259	SMC-07-46	AK07-10425KY		4.1	0.97	30	30	10	0.09	6	2	236	7	1.09	0.03 <10	0.04	86	2	0.02	8	60	1462	10 <20	16 <0.01	<10	2 <10	<1	411				
REG26268	SMC-07-46	AK07-10425KY	>30		0.03	125 <5		310	0.01	7	13	313	152	1.46	0.02 <10	0.01	151	3 <0.01	50	80 >10000	60 <20	5 <0.01	<10	4 <10	<1	42						
REG26285	SMC-07-46	AK07-10425KY	>30		0.99	60	70	15	0.1	17	1	512	656	1.16	0.14 <10	0.01	93	6	0.01	11	150 >10000	490 <20	23 <0.01	<10	9 <10	<1	1058					

Tag #	Shipno	Certificate	Au (g/t)	Ag	Al	As	Ba	Bi	Ca	Cd	Co	Cr	Cu	Fe	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	Sb	Sn	Sr	Tl	U	V	W	Y	Zn
RESG26251	SMC-07-46	AK07-10425KY	0.07	8.7	0.43	15	40	10	0.02	<1	2	418	6	0.86	0.05	<10	0.02	203	2	0.01	15	50	2152	15	<20	3	<0.01	<10	3	<10	<1	10
RESG26252	SMC-07-46	AK07-10425KY																														
RESG26285	SMC-07-46	AK07-10425KY	34.1	>30	0.94	70	85	20	0.1	19	<1	493	671	1.07	0.07	<10	0.01	96	6	0.01	9	150	>10000	540	<20	27	<0.01	<10	7	<10	<1	1012

JJ/nl
df/td1042S
XLS/06

ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer