



Ministry of Energy & Mines
Energy & Minerals Division
Geological Survey Branch

ASSESSMENT REPORT
TITLE PAGE AND SUMMARY

TITLE OF REPORT [type of survey(s)] <u>Turnagain Property Diamond Drill Report</u>		TOTAL COST <u>\$1,438,081.31</u>
AUTHOR(S) <u>G. Ross, J.E. Scheel</u>	SIGNATURE(S)	
NOTICE OF WORK PERMIT NUMBER(S)/DATE(S) <u>MX-1-505, SM1-08-0100439-0807</u>		YEAR OF WORK <u>2008</u>
STATEMENT OF WORK - CASH PAYMENT EVENT NUMBER(S)/DATE(S) <u>4247381</u>		
PROPERTY NAME <u>Turnagain</u>		
CLAIM NAME(S) (on which work was done) <u>511330 511344 570455</u>		
COMMODITIES SOUGHT <u>Ni Co Cu Pt Pd</u>		
MINERAL INVENTORY MINFILE NUMBER(S), IF KNOWN <u>104I014</u>		
MINING DIVISION <u>Liard</u>	NTS <u>104I7W</u>	
LATITUDE <u>58</u> ° <u>28</u> ' <u>30</u> " LONGITUDE <u>-128</u> ° <u>51</u> ' <u>15</u> " (at centre of work)		
OWNER(S)		
1) <u>Hard Creek Nickel Corp</u>	2) _____	
MAILING ADDRESS		
<u>1060 - 1090 W. Georgia Street</u>		
<u>Vancouver BC V6E 3V7</u>		
OPERATOR(S) [who paid for the work]		
1) <u>Hard Creek Nickel Corp</u>	2) _____	
MAILING ADDRESS		
<u>as above</u>		
PROPERTY GEOLOGY KEYWORDS (lithology, age, stratigraphy, structure, alteration, mineralization, size and attitude):		
<u>Turnagain ultramafic complex, Alaskan-type, dunite, wehrlite, pyroxenite, disseminated sulphide, intercumulous sulphide, pentlandite, pyrrhotite, mid- to late-Jurassic, fault-bounded.</u>		
REFERENCES TO PREVIOUS ASSESSMENT WORK AND ASSESSMENT REPORT NUMBERS <u>2056 3206 3735</u>		
<u>4097 8055 15994 15458 24911 25475 27646 28101 28840 29748</u>		

TYPE OF WORK IN THIS REPORT	EXTENT OF WORK (IN METRIC UNITS)	ON WHICH CLAIMS	PROJECT COSTS APPORTIONED (incl. support)
-----------------------------	----------------------------------	-----------------	---

GEOLOGICAL (scale, area)

Ground, mapping _____
 Photo interpretation _____

GEOPHYSICAL (line-kilometres)

Ground
 Magnetic _____
 Electromagnetic _____
 Induced Polarization _____
 Radiometric _____
 Seismic _____
 Other _____
 Airborne _____

GEOCHEMICAL

(number of samples analysed for ...)

Soil _____
 Silt _____
 Rock _____
 Other _____

DRILLING

(total metres; number of holes, size)

Core 4,025.20 m 511330 570455 \$1,430,890.90
 Non-core 20.12 m 511344 \$ 7,190.42

RELATED TECHNICAL

Sampling/assaying _____
 Petrographic _____
 Mineralographic _____
 Metallurgic _____

PROSPECTING (scale, area)

PREPARATORY/PHYSICAL

Line/grid (kilometres) _____
 Topographic/Photogrammetric (scale, area) _____
 Legal surveys (scale, area) _____
 Road, local access (kilometres)/trail _____
 Trench (metres) _____
 Underground dev. (metres) _____
 Other _____

TOTAL COST \$1,438,081.31

BC Geological Survey
Assessment Report
30367

TITLE: 2008 DIAMOND DRILLING REPORT ON
THE TURNAGAIN PROPERTY

CLAIMS WORKED: 511330, 511344, 570455

RECORD NUMBERS: 511330, 511344, 570455

MINING DIVISION: LIARD

NTS MAP SHEET: 104I/07W

MINERAL TITLES
REFERENCES MAP: M104I 046

LATITUDE: 58°27' - 58°30'

LONGITUDE: 128°48' - 128°56'

CLAIM OWNER: HARD CREEK NICKEL CORP. (#103195)

OPERATOR: HARD CREEK NICKEL CORP.

DATE SUBMITTED: 29 July 2009

AUTHORS: G. Ross, J.E. Scheel

TABLE OF CONTENTS

	Page
INTRODUCTION	1
PROPERTY DESCRIPTION AND ACCESS	1
PREVIOUS WORK	1
GEOLOGICAL SETTING	6
REGIONAL GEOLOGY	6
PROPERTY GEOLOGY	7
MINERALIZATION	7
2007 DIAMOND DRILLING PROGRAM	9
ANALYTICAL TECHNIQUES	9
DRILL HOLE RESULTS	10
CONCLUSIONS	14
RECOMMENDATIONS	15
REFERENCES	16

List of Figures

	Page	
Figure 1	General Location - Turnagain Property	2
Figure 2	Claim Map - Turnagain Property	3
Figure 3	Claim Map - 1:50,000	4
Figure 4	Property Geology and Occurrences	8
Figure 5	Drill Hole Location Map	11

Appendices

Appendix A	Claims List	17
Appendix B	Drill Logs	20
Appendix C	Downhole Surveys	93
Appendix D	Cross Sections	129
Appendix E	Analytical Method and Results	142
Appendix F	Statement of Costs	455
Appendix G	Statements of Qualifications	457

INTRODUCTION

The Turnagain Property of Hard Creek Nickel Corp. (previously named Canadian Metals Exploration Limited) has been sporadically explored for nickel-copper-platinum-palladium mineralization since the mid-1960s. Disseminated interstitial sulphide grains and blebs are the most widespread type of mineralization within the ultramafic suite of rocks. In some locations, sulphide blebs coalesce to produce net-textured to locally massive sulphide intervals in dunite, wehrlite and olivine clinopyroxenite. Where disseminated sulphides occur in dunite or wehrlite, nickel sulphide (principally pentlandite) is commonly present in sufficient concentrations to be of economic interest.

For the past several years Hard Creek Nickel Corp. has been conducting diamond drilling programs focused mainly on the Horsetrail and Northwest Zones, known zones of low grade nickel mineralization north of the Turnagain River in the southeast portion on the intrusion, as well as other prospective areas of the intrusion. This report describes 16 holes from Hard Creek Nickel Corp.'s 2008 diamond drilling program, comprising 4,105.32 m of drilling.

PROPERTY DESCRIPTION AND ACCESS

The Turnagain Property is located in the Liard Mining Division, 65 km east of the community of Dease Lake and 1,350 km north-northwest of Vancouver (Figure 1). The property covers approximately 29,600 ha, spread across mineral titles maps 104I 03, 104I 046, 104I 047, 104I 055 and 104I 056 and is comprised of one four-post claim and 56 electronically acquired claims. Claim details are summarized in Appendix A and their locations are illustrated in Figures 2 and 3.

The property can be accessed by helicopter and fixed-wing aircraft from Dease Lake to a recently upgraded 930 m long gravel airstrip located beside the exploration camp and core storage. During the drier months, access via the Turnagain River – Kutcho Creek mining road from Dease Lake is possible. Several drill roads provide access to portions of the property on both sides of the Turnagain River.

An exploration camp was constructed on the property in April, 2003. Prior to this date, exploration was based in the placer mining camp located at Wheaton Creek (Boulder City) some 15 km southwest of the property. All core drilled before late April, 2003, by previous operators and Canadian Metals, is stored at the placer camp. The majority of the core from 2003 program and all core from the 2004 – 2008 drill programs is stored in core racks beside the airstrip on the Turnagain Property.

The Turnagain resource area covers a south-facing slope which begins just above 1,780 m elevation and extends down to the Turnagain River at 1,000 m elevation.

Outcrop exposure is abundant between tree line and the ridge crest but, except for approximately one percent exposure in the Horsetrail area, is poor over most of the claim block located west of the Turnagain River. Exposure is abundant on the low ridge extending east from the Turnagain River in the Cliff Zone.


PREVIOUS WORK

Nickel and copper sulphides were first recognized in rusty weathering exposures of the Discovery Showing on the bank of the Turnagain River in about 1956. Falconbridge Nickel Mines acquired the property in 1966 and, during the next seven years, completed an airborne geophysical survey, ground geophysical surveys, geological mapping, geochemical surveys and 2,895 m of diamond drilling in approximately 28 widely spaced holes (McDougall and Clark, 1972, 1973). During the early 1970s, adjacent claims were investigated with a geochemical survey by Union Minière Exploration and Mining Corporation Ltd (UMEX) (Burgoyne, 1971). Once the Falconbridge and UMEX claims expired, a number of showings were re-staked and tested with



Figure 1

HARD CREEK NICKEL CORP.	
Turnagain Ni-Co-PGE Project Liard M.D., British Columbia	
Date: 5/2/2008	Location Map
Author: GPR	
Office: HNC	
Drawing: 1 of 5	
Scale: as shown	






Figure 3
HARD CREEK NICKEL CORP.

Date: 18/11/2008	Turnagain Ni-Co-PGE Project Claim Map Showing Areas of Work
Author: GPR	
Office: HNC	
Drawing: 3 of 5	
Scale: 1:50000 Projection: UTM Zone 9 (NAD 83)	

0 0.5 1 2
kilometres

short, small diameter core holes. Three EX-sized core holes totaling 55.5 m were drilled on the left bank of the Turnagain in 1977 (Brown, 1978). No significant intersections were reported and the collars have not been located. In 1979 a single drill hole of 17 m depth was drilled near the right bank of the Turnagain River and intersected unmineralized quartz diorite (Cukor, 1980).

By the mid-1980s, exploration interest shifted to platinum group elements. The Falconbridge core was re-sampled and a geochemical survey for platinum group elements was conducted for Equinox Resources Ltd (Cukor, 1987;1986).

In 1996 Bren-Mar Resources Ltd (predecessor to Canadian Metals Exploration Ltd) optioned the Cub claim from J. Schussler and E. Hatzl. Between 1996 and 1998 Bren-Mar completed an airborne magnetic survey over 45 sq. km, 19 core holes totaling 3,889 m, down-hole pulse electromagnetic surveys in four of the 1997-1998 drill holes and preliminary metallurgical test work on drill core composite samples (Livgard, 1996; Downing, 1998).

Canadian Metals Exploration Ltd resumed exploration in 2002 with an induced polarization and ground magnetic survey followed by 1,687 m of diamond drilling in seven holes (Downing, 2003; Woods, 2003). The 2003 exploration program emphasized diamond drilling and resulted in 23 holes, including the deepening of one 2002 hole, for a total of 8,769 m. Results from three drill holes were documented by Canadian Metals in 2004 (Baldys and Hitchins, 2004).

Hard Creek Nickel Corp. conducted a comprehensive exploration program over the claim block in 2004 (Assessment Report # 27646) including:

- 1,700 line-km of helicopter-borne magnetic and electromagnetic surveys
- 14 line-km of detailed ground magnetometer, transient EM and VLF surveys over the Horsetrail Zone.
- transient EM surveys in nine boreholes
- collection of approximately 3,000 soil samples
- several lines of biogeochemical sample collection
- geological mapping of the exposed ultramafic lithologies
- 1:20,000 scale air photography and preparation of base maps
- 7,387 m of core drilling in 49 holes
- more than 4,000 core samples analyzed for 30 elements including Ni, Cu, Co, S, Pt and Pd

The 2005 exploration program was similarly extensive (Assessment Report # 28101) and included:

- follow-up prospecting and interpretation of geophysical targets
- further borehole transient EM surveys in 13 holes for a total of 7,400 m
- more than 1,900 infill soil geochemistry samples
- continued geological mapping
- 7,144 m of BQ and NQ diamond drilling in 37 holes
- more than 3,700 core samples analyzed for 30 elements including Ni, Cu, Co, S, Pt and Pd

The 2006 exploration program was somewhat more extensive (Assessment Report # 28840) and included:

- further prospecting and interpretation of geophysical targets
- small program of infill soil sampling
- continued geological mapping
- 19,121.8 m of NQ diamond drilling in 69 holes
- more than 4,500 core samples analyzed for 30 elements including Ni, Cu, Co, S, Pt and Pd

The 2007 exploration program was more extensive still (Assessment Report # 29748) and included:

- further prospecting
- continued geological mapping
- 24,869.9 m of NQ and PQ diamond drilling in 73 holes
- metallurgical and grinding test of PQ composite samples
- more than 6,000 core samples analyzed for 30 elements including Ni, Cu, Co, S, Pt and Pd

The 2008 exploration program was downsized from previous years and included:

- continued geological mapping
- 4,105 m of NQ and HQ diamond drilling
- the installation of two groundwater monitoring wells
- continued metallurgical testing including flotation and recovery tests
- more than 1,025 core samples analyzed for 30 elements including Ni, Cu, Co, S, Pt and Pd

GEOLOGICAL SETTING

Regional Geology

The Turnagain Resource is hosted by an ultramafic complex of Early Jurassic age (Scheel, 2007) within Paleozoic metasedimentary and metavolcanic rocks assigned to the Road River Formation along the faulted terrane boundary between the cratonic margin and accreted terrane (Gabrielse, 1998). Hornfelsed metasediments found within the ultramafic complex are Early Permian (Scheel, 2007). There has been some uncertainty as to the age and origin of the Paleozoic rocks adjacent to the Turnagain ultramafic complex and Nixon (1998) has presented two interpretations. One interpretation suggests that the Paleozoic rocks are autochthonous and range in age from Cambrian to Upper Paleozoic – Triassic. An alternative interpretation, and the one favoured by Nixon, places the Turnagain ultramafic complex within an imbricated sequence of Late Paleozoic to Triassic sedimentary and volcanic rocks which were thrust eastward onto the margin of the North American craton. Support for this latter interpretation comes in part from the belief that the Turnagain ultramafic body is a zoned Alaskan-type complex and that other known examples in the northwestern Cordillera occur in accretionary terranes. Despite the differing interpretations, both place the Turnagain ultramafic body proximal to a major terrane boundary, a geological environment similar to many of the major nickel-bearing ultramafic intrusions of the Canadian Shield.

A number of non-zoned, apparently alpine-type ultramafic bodies are exposed in rocks of the Cache Creek terrane, south and west of the Turnagain ultramafic body. Most of these are strongly serpentized and host a number of asbestos and jade occurrences.

Property Geology

The property covers the known extent of a zoned Alaskan-type ultramafic intrusion, which measures 8 km by 3 km and is elongate in a northwest direction, conformable to the regional structural grain. The ultramafic body is in fault contact with Paleozoic(?) graphitic metasedimentary rocks along its northern and eastern margins. The southern contact is poorly exposed but several drill holes have penetrated the contact and intersected deformed, graphitic, phyllitic rocks in fault contact with the ultramafic body. Locally, the phyllitic rocks display a weak brownish cast, suggestive of minor thermal alteration. Within the intrusion, hornfelsed metasediments of uncertain affinity show a range of stronger thermal effects.

The ultramafic complex consists of a central, well-exposed dunite core and an outer zone of more poorly exposed dunite, wehrlite, olivine clinopyroxenite, clinopyroxenite and hornblendite. Poorly exposed hornblendite and clinopyroxenite dominate the south-central portion of the complex (Figure 4). All of these rock types and gradations between them have been interpreted as crystal cumulates (Clark, 1980; Nixon, 1998). Narrow bands and schlieren of millimetre-sized chromite crystals have been noted in dunite exposures and drill core. Phlogopite is a minor accessory mineral but is locally conspicuous in dunite and wehrlite.

Alteration varies from weak to intense serpentinization with several types of serpentine present. Generally, serpentinization is not intense. Most of the prominent magnetic anomaly coinciding with the ultramafic generally results from magnetite produced during serpentinization rather than from cumulus magnetite. Talc replacement of narrow felsic dykes, some faults and adjacent wallrock is often intense and is interpreted to be later than most of the serpentine alteration.

Fine-grained tremolite often occurs with serpentine alteration but comprises the majority of some core intervals, particularly where clinopyroxenite appears to have been present originally.


The Turnagain ultramafic body is considered to be an Alaskan-type intrusion due to the following features (Nixon, 1998):

- orthopyroxene is lacking
- clinopyroxene compositions are diopsidic and comparable to other Alaskan-type intrusions
- ultramafic cumulates are restricted to mixtures of olivine and clinopyroxene with minor chromite, rare amphibole and trace phlogopite
- localized chromitite layers in the dunite have been remobilized to form schlieren and syndepositional folds, features that are characteristic of all Alaskan-type intrusions in British Columbia

The Turnagain intrusion is broadly zoned but, with a few local exceptions, generally lacks fine original structures such as magmatic layering.

MINERALIZATION

The Turnagain intrusion differs from most other Alaskan-type intrusions in at least one important aspect: it hosts half a dozen known occurrences of magmatic pyrrhotite-pentlandite-chalcopyrite mineralization (Figure 4). In drill core these sulphides generally occur as disseminated zones of interstitial to blebby sulphides that locally coalesce to form net-textured zones of sulphides enclosing silicate grains. Short sections of semi-massive to massive sulphides are occasionally in contact with overlying(?) net-textured sulphides and rarely in sharp contact with only weakly disseminated sulphides. The latter occurrences are interpreted to be the result of the remobilization of primary interstitial sulphide into fractures or shears during deformation and, in rare cases, may represent original massive sulphide horizons or pods. The host rock of most of the disseminated to interstitial mineralization is dark grey coloured dunite and wehrlite. Low-grade sulphide-rich intercepts are commonly adjacent to, or within, more pyroxene-rich



Legend

- Di - diorite with minor quartz diorite, tonalite and granodiorite
- Du - dunite with minor wehrlite
- Sp - serpentinite, dunite protolith
- Wh - wehrlite with minor dunite and olivine clinopyroxenite
- mtcPx - magnetite clinopyroxenite and hornblende clinopyroxenite, undivided
- cPx - olivine clinopyroxenite and clinopyroxenite, undivided
- Hfs - hornfels, volcanic wacke protolith
- Hb - hornblendite
- Phy - graphitic, locally pyritic phyllite with minor tuff and siltstone
- Wk - volcanic wacke to tuffaceous phyllite

- ★ Mineral occurrence
- - - - - inferred lithologic contact
- — — — — observed lithologic contact
- - - - - inferred fault
- — — — — observed fault
- ▲▲▲▲▲ inferred thrust fault
- ▲▲▲▲▲ observed thrust fault



Figure 4

HARD CREEK NICKEL CORP.

Date: 5/2/2008	Turnagain Ni-Co-PGE Project Geology and Mineral Occurrences
Author: GPR	
Office: HNC	
Drawing: 1 of 1	
Scale: 1:20000	
Projection: UTM Zone 9 (NAD 83)	

lithologies, whereas high-grade sulphide-rich intercepts are typically observed in serpentinized dunite and wehrlite.

Short intervals of vein or massive pyrrhotite, usually with varying amounts of veinlet-stringer chalcopyrite, massive graphite and blebby to massive magnetite, are spatially related to faults and zones of intense serpentine-tremolite alteration. These sulphide occurrences usually have a lower pentlandite/pyrrhotite ratio than primary sulphide intervals and might represent partial remobilization from nearby primary sulphides during a post-magmatic event.

2008 DIAMOND DRILL PROGRAM

This report documents 16 holes from the 2008 diamond drilling program conducted from 4 June 2008 to 27 August 2008. DJ Drilling of Aldergrove, BC supplied the crews and equipment. The drill rigs used were one skid-mounted LF125 drilling NQ-size core and one LF90 helicopter fly-rig drilling both NQ- and HQ-size core. A Bell 206B helicopter from Pacific Western Helicopters of Dease Lake was used for fly drill moves and crew changes for holes 08-249 to 08-253 and for drill moves for holes 08-262 to 08-264. Recoveries were generally better than 95% and down hole surveys indicate that holes generally deviated only a few metres from collar to end of hole. The 2007 targets consisted of AeroTEM conductors, magnetic anomalies, potential extensions of known mineralization and infill drilling in the Horsetrail Zone.

Analytical Techniques

All core was split into four metre or shorter sample intervals and the bagged samples were shipped by helicopter and truck to Acme Analytical Laboratories Ltd in Smithers, BC for preparation and Vancouver, BC for analyses for as many as 30 elements. Most elements were determined by ICP-emission spectrometry following four-acid digestion (HF-HClO₄-HNO₃-HCl). Platinum, palladium and gold were measured by ICP-ES following lead collection fire assay fusion of a 30 g sample.

Since ICP-ES analysis for nickel and cobalt following four-acid digestion includes nickel and cobalt from both silicate minerals (mainly olivine) and sulphide minerals, a second sample pulp was subjected to a sulphide-specific digestion involving ammonium citrate-hydrogen peroxide.

Analytical results were considered to be of exploration significance when nickel results from the four-acid digestion were $\geq 0.25\%$ and were supported by sulphur values $\geq 0.20\%$. Generally, when these two conditions are satisfied more than 70% of total nickel occurs in sulphide minerals. Certificates of analyses for all elements and descriptions of Acme's analytical methods are included in Appendix E.

Ten percent of the sample pulps were check-analyzed by iPL of Richmond, BC. Comparison analytical results for reference standards between the two laboratories were within ten percent of accepted values. Nickel blanks and standards were inserted in the sample sequence every 30 and 25 samples, respectively, and duplicate pulps were analyzed every 30 samples as part of the QC/QA procedure.

Drill Hole Results

Locations below are given in UTM coordinates (Zone 9, NAD 83) and shown in Figure 5. A summary of the 21 holes is presented below and the reader is referred to Appendix B for the detailed drill logs.


Hole	Easting	Northing	Elevation /m	Azimuth /°	Inclination /°	Depth /m	Drill Used	Diameter
08-249	511005	6481593	1149.6	180.0	-50.0	370.4	LF90	NQ
08-250	510798	6481719	1130.7	181.4	-50.0	182.0	LF90	NQ
08-251	510337	6481746	1041.8	179.9	-85.0	000.0	LF90	NQ
08-252	511299	6481511	1165.0	178.6	-50.0	254.8	LF90	NQ
08-253	510907	6481452	1137.4	180.5	-50.0	273.7	LF90	NQ
08-254	508860	6481420	1103.7	181.5	-47.9	318.5	LF125	NQ
08-255	508797	6481439	1114.7	181.4	-50.7	358.2	LF125	NQ
08-256	508746	6481425	1122.8	180.9	-49.7	327.7	LF125	NQ
08-257	508901	6481436	1103.2	181.3	-49.5	273.4	LF125	NQ
08-258	508960	6481431	1092.0	180.5	-51.6	275.9	LF125	NQ
08-259	508942	6481310	1082.6	180.9	-47.3	300.9	LF125	NQ
08-260	508746	6481323	1104.9	178.6	-50.2	333.8	LF125	NQ
08-261	508595	6481382	1130.5	179.7	-50.3	419.1	LF125	NQ
08-262	507845	6479427	1018.1	177.2	-90.0	020.1	LF90	HQ
08-263	509129	6481155	1022.6	179.4	-90.0	152.1	LF90	HQ
08-264	508876	6481061	1038.5	358.3	-04.5	245.1	LF90	NQ

Hole 08-249 was drilled as a step-out from holes 07-237, 238, and 239 to test for a possible eastward extension of mineralization in the Cliff Zone. The top 140 m of the hole is generally weakly to moderately mineralized but punctuated by local high grade intercepts of 4 - 8 m, and is composed of variably serpentine- and tremolite-altered dunite and wehrlite cross-cut by olivine clinopyroxenite and clinopyroxenite. Visual sulphide estimates increased 140 m - 211.65 m, coincident with elevated Pt+Pd (2.26 g/t over 64 m), Ni (0.307 % over 48 m), and Cu (0.162 % over 48 m) values. Afterwards one high-sulphide/grade intercept from 238.20 - 249.70 m was intersected within weakly mineralized, tremolite- and serpentine-altered dunite. The fault contact between the ultramafic and country rock was intercepted at 348.20 m.

Hole 08-250 was also drilled as a step-out from holes 07-237, 238, and 239 to test for a possible northwestward extension of previously intersected mineralization. Hole 08-250 intersected variably serpentine- and tremolite-altered dunite, with no observed sulphide until 66.35 m depth, and trace sulphides to EOH at 181.95 m. No significant results were returned, and hole 08-250 failed to extend known mineralization. The near-complete lack of sulphides in this hole suggests the mineralization intersected in holes 07-237, 238, and 239 was cut off by a north-trending fault between 08-250 and the 2007 holes.

Hole 08-251 was drilled at the base of a large steep rock face to test AeroTEM conductors to its south and to determine (if possible) the position of the contact between the interpreted clinopyroxene-rich southern, and olivine-rich northern, portions of the Cliff Zone. The original inclination of the hole (-50) was revised to -65 after casing was lost due to difficult overburden. The attempt at -65 was subsequently revised to -85 due to the same problem. When the drilling proved still too difficult at -85 the hole was abandoned, never having penetrated to bedrock.

Hole 08-252 was drilled far to the east of mineralization intersected in holes 07-237, 238, and 239 to possibly extended, or discover new, mineralization. The hole broadly consisted of weakly mineralized serpentine- and tremolite-altered dunite to 126.20 m. Weakly mineralized



Legend

- Di - diorite with minor quartz diorite, tonalite and granodiorite
- Du - dunite with minor wehrlite
- Sp - serpentinite, dunite protolith
- Wh - wehrlite with minor dunite and olivine clinopyroxenite
- mtcPx - magnetite clinopyroxenite and hornblende clinopyroxenite, undivided
- cPx - olivine clinopyroxenite and clinopyroxenite, undivided
- Hfs - hornfels, volcanic wacke protolith
- Hb - hornblendite
- Phy - graphitic, locally pyritic phyllite with minor tuff and siltstone
- Wk - volcanic wacke to tuffaceous phyllite

- inferred lithologic contact
- observed lithologic contact
- inferred fault
- observed fault
- ▲▲▲▲▲ inferred thrust fault
- ▲▲▲▲▲ observed thrust fault




Figure 5

HARD CREEK NICKEL CORP.	
Turnagain Ni-Co-PGE Project	
Date: 24/11/2008	Geology and Drill Hole Plan
Author: GPR	
Office: HNC	
Drawing:	
Scale: 1:12500	Projection: UTM Zone 9 (NAD 83)

clinopyroxenite with some wehrlite was intersected to 141.65 m. The rest of hole 08-252 was dominantly weakly mineralized serpentine- and tremolite-altered wehrlite. Elevated Pt+Pd and slightly elevated Ni values were intersected from 224.70 - 245.35 m, grading 1.54 g/t Pt+Pd and 0.163 % sulphide Ni. The wehrlite ended in possible fault contact with metasedimentary rocks at 250.60 m. In general, hole 08-252 intersected new mineralization.

Hole 08-253 was drilled south of holes 07-237, 238, and 239 to test for a possible southward extension of previously encountered mineralization, and to test an AeroTEM conductor. The top 34 m of the hole intersected weakly mineralized dunite and wehrlite cross-cut by a fault at 14.0 - 17.0 m. From 34.25 m to 64.50 m, weakly mineralized tremolite- and serpentine-altered olivine clinopyroxenite was encountered. A similarly altered, weakly mineralized wehrlite was intersected to 101.95 m. Clinopyroxenite was then encountered to 129.30, but contained an altered felsic dike 103.35 - 116.10 m and a fault 116.10 m - 122.30 m which contained a mixture of dunite and clinopyroxenite. From 122.30 to 199.80 m, hole 08-253 intersected significant weakly mineralized dunite, followed by similarly mineralized wehrlite to 205.60 m, with a small fault at 187.40 m. Weakly mineralized, tremolite-altered clinopyroxenite and olivine clinopyroxenite was intersected from to 238.90 m. From 238.90 m to EOH at 273.70 m, hole 08-253 was dominated by serpentine- and tremolite-altered wehrlite with some dunite or olivine clinopyroxenite intersections. Hole 08-253 failed to extend previously intersected mineralization, but did confirm the presence of significant clinopyroxene-rich lithologies in the southern portion of the Cliff Zone. This hole generally exhibits low Ni grades with anomalous to elevated Pt+Pd values and local Cu enrichment.

Hole 08-254 was drilled in the northern Horsetrail Zone with the purpose, as with the other holes drilled in this area in 2008, to upgrade the current resource estimates and delineate high-grade intercepts previously drilled. Hole 08-254 collared in weakly mineralized serpentinized dunite to 30.50 m, and drilled through green dunite to 192 m, most of which was also weakly mineralized. Weakly to moderately mineralized serpentinized wehrlite and dunite were intersected from 192 m to EOH at 318.5 m. From 220 to EOH, the intersection grades 0.219 % sulphide Ni and 1.11 g/t Pt+Pd, with some analyses returning significant results (260 – 272 m grades 0.341 % sulphide Ni and 1.36 g/t Pt+Pd). In general, hole 08-254 confirmed the presence of high grade Ni-sulphide mineralization in the deeper parts of the Horsetrail Zone.

Hole 08-255 was drilled 50 m to the west of hole 08-254, and collared in weakly mineralized serpentinized wehrlite to 45.05 m, where it is intensely intruded by diorite dikes and proceeded by wehrlite to 68.50 m. Sulphide contents are below 1 % for the above intercepts. After an 8 m intercept of serpentinized wehrlite, the hole is dominated by weakly mineralized serpentinized dunite to a depth of 125.40 m. Weakly mineralized serpentinized wehrlite was intersected to 166.0 m, where tremolite alteration becomes prevalent. Tremolite-serpentine-altered wehrlite, weakly mineralized, was intersected to 198.20 m, followed by tremolite-altered wehrlite to 213.80 m. A sudden increase in sulphide and pentlandite content was observed to 281.90 m, and the lithologies intersected were tremolite-altered dunite (213.80 - 235.50 m), tremolite-altered wehrlite with graphite-sulphide inclusions (to 269.65 m), and serpentinized dunite with graphite-sulphide (to 281.90 m). This entire ~68 m package exhibited some of the highest grade results to date in terms of both Ni and Pt-Pd (0.503 % sulphide Ni and 1.08 g/t Pt+Pd over 44 m). Proceeding this package is a long intercept of serpentinized dunite variably cross-cut by diorite and clinopyroxenite dikes, to EOH at 358.15 m, with no significant results. Hole 08-255 successfully delineated a major high-grade zone within the deeper reaches of the Horsetrail Zone.

Hole 08-256 was drilled 50 m to the west of hole 08-255, and intersected weakly mineralized dunite, olivine clinopyroxenite, and serpentinized wehrlite to 29.70 m. Weakly mineralized serpentinized wehrlite, olivine clinopyroxenite, and variably serpentinized dunite were intersected to 150.0 m. Clinopyroxenite and tremolite-altered olivine clinopyroxenite, followed by tremolite-altered wehrlite, all weakly mineralized, were intersected to 187.10 m., with high sulphide contents (4- 7 %) encountered in the pyroxene-rich units. Well-mineralized serpentinized wehrlite and dunite were intersected to 214.0 m. These units were characterized by net-textured sulphides

with pentlandite contents between 1 and 5 %, and assays of over 1 % sulphide Ni. A small intersection of weakly mineralized gray dunite yielded to well-mineralized dunite containing blebby sulphides up to 11 % and good Ni grades. Variably serpentinized dunite followed, intruded by diorite dikes, to 290.45 m, and contained a moderately mineralized interval between 260 - 276 m. Another gray dunite unit was encountered which exhibited good Ni and PGE assays and a sulphide content of 0.5 - 4 %, to 312.90 m. This unit was proceeded by a fault, which extended almost to EOH at 327.65 m. In general, hole 08-256 delineated three separate Ni-sulphide-mineralized zones beneath the Horsetrail Zone.

Hole 08-257 was drilled 50 m to the east of hole 08-254 and collared in weakly mineralized dunite to 64 m, and proceeded to intercept weakly mineralized green dunite to 84 m. This sequence was repeated to 180 m, until weakly mineralized serpentinized dunite was intersected to 212 m. After more green dunite (to 240 m), variably tremolite- and serpentine-altered wehrlite was intersected to EOH at 273.4 m. Hole 08-257 failed to intersect moderate- or high-grade mineralization at depth in the Horsetrail Zone.

Hole 08-258 was drilled 50 m to the east of hole 08-257. This hole collared in unmineralized to weakly mineralized dunite, with some small serpentinized intercepts, to 88 m. Varying amounts of unmineralized olivine clinopyroxenite (mixed with dunite) were encountered to 105.80 m, when a small dike was intersected. Afterwards, moderate- to high-grade serpentinized dunite was intersected to 141.7 m, and included a 4 m sample grading 1 % sulphide Ni, 0.19 % sulphide Cu, and 0.45 g/t Pt+Pd. A high grade intersection of olivine clinopyroxenite was intersected immediately afterwards, and was followed by moderate to high grade dunite, containing significant graphite, to 154.40 m. Weakly mineralized wehrlite and dunite were encountered to 200.00 m, where tremolite alteration became significant. A mixture of serpentine- and/or tremolite-altered wehrlite, dunite, and olivine clinopyroxenite, all weakly mineralized, was intercepted to EOH at 275.85 m. Hole 08-258 succeeded at confirming high-grade mineralization at depth in the Horsetrail Zone.

Hole 08-259 was drilled approximately 120 m south of hole 08-258. It collared in serpentinized green dunite and proceeded to intercept green dunite to 21.65 m, which was followed by serpentinized dunite to 29.45 m. Variably tremolite- and serpentine-altered wehrlite and some dunite was intercepted to 90.15 m, all of which was weakly mineralized. Unmineralized hornfels and altered olivine clinopyroxenite and clinopyroxenite was intersected to 136.10 m. Serpentine- and tremolite-altered dunite, with significant sulphide mineralization (3 - 7 % sulphide), was intersected to 242.85 m. This intersection contained 104 m grading 0.303 % sulphide Ni, including 24 m of 0.461 % sulphide Ni with 1.36 g/t Pt+Pd. This intersection was followed by weakly-mineralized, tremolite-altered wehrlite and olivine clinopyroxenite to 290.45 m. Weakly to moderately mineralized serpentinized dunite was intersected to EOH at 300.85 m. Hole 08-259 was successful in confirming and further defining high-grade mineralization in the Horsetrail Zone.

Hole 08-260 was drilled 100 m south of hole 08-256 and collared in weakly serpentinized and moderately mineralized dunite to 16.75 m. Moderately mineralized tremolite-altered wehrlite was intersected to 77.50 m. Within this unit, 20 m of wehrlite containing graphite-sulphide inclusions graded 0.393 % sulphide Ni with 1.26 g/t Pt+Pd. Tremolite-altered dunite was intersected 77.50 - 105.60 m, and was moderately mineralized with a short 4 m interval grading 0.483 % sulphide Ni. Tremolite-altered wehrlite (to 124.50 m) and dunite (to 153.60 m) proceeding the previous intersection were weakly mineralized. Moderately to strongly mineralized tremolite- and serpentine-altered dunite and wehrlite were intersected to 173.60 m. The dunite contained graphite-sulphide inclusions and the package graded 0.320 % sulphide Ni and 0.103 % sulphide Cu over 16 m. Weakly mineralized and variably altered dunite and minor wehrlite, cross-cut by felsic dikes, were intersected to 202.55 m, followed by unmineralized and unaltered dunite to 230.95 m. Weakly to moderately mineralized serpentinized dunite was intersected to EOH at 333.75 m, with the bottom 73.75 m grading 0.230 % sulphide Ni. Hole 08-260 was successful in confirming previously inferred resource at depth in the Horsetrail Zone.

Hole 08-261 was drilled 155 m west-southwest of hole 08-256 and collared in variably serpentinized, unmineralized to weakly mineralized to green dunite to 69.20 m. Tremolite-altered dunite, with weak sulphide mineralization, was intercepted to 85.15 m. Moderately mineralized serpentinite, probably after dunite and related to a fault zone, was intercepted to 101.60 m. The fault itself was intersected from 86.80 - 100.00 m. Moderately mineralized tremolite-altered dunite proceeds the serpentinite to a depth of 136.85 m. Although trace amounts of sulphide were recorded in this interval, the sulphide Ni results suggest all the sulphide occurs as pentlandite. After a short interval of weakly mineralized tremolite- and serpentine-altered dunite (to 144.90 m), a very long interval of moderately to strongly mineralized tremolite- and serpentine-altered dunite was intersected to 270.00 m, grading 0.249 % sulphide Ni over 124 m and including two 16 m intercepts of grading >0.3 % sulphide Ni. This long mineralized intercept is preceded by similarly-altered dunite but with weak sulphide mineralization to 287.30 m. A short fault (to 291.65 m) and preceding graphite-sulphide-bearing olivine clinopyroxenite (to 293.10 m) returned grades of 0.313 % and 0.544 % sulphide Ni, respectively. The latter was observed to contain 1 % pentlandite. Weakly mineralized tremolite-altered olivine clinopyroxenite was intersected to 318.45 m, followed by tremolite-altered wehrlite to 325.85 m. Strongly mineralized variably tremolite- and serpentine-altered dunite was intersected to 391.80 m, and graded 0.304 % sulphide Ni over 68 m. Weakly mineralized graphitic tremolite-altered dunite was intersected to 402.60 m, followed by weakly mineralized tremolite- and serpentine-altered dunite to EOH at 419.10 m. Hole 08-261 was successful at defining two separate zones of moderate to high grade mineralization at depth in the Horsetrail Zone.

Hole 08-262 was drilled approximately 850 m to the south-southwest of Turnagain camp, and was drilled as a water monitoring well, to a depth of 20.12 m. The hole never penetrated to bedrock.

Hole 08-263 was drilled 325 m to the southeast of hole 08-258, and was drilled for water monitoring purposes. The hole collared in olivine clinopyroxenite to 5.05 m, and intersected serpentinized wehrlite and dunite to 26.15 m. Tremolite-altered olivine clinopyroxenite, with minor amounts of dunite and wehrlite, were intersected to 135.30 m. Moderately to intensely talc-altered olivine clinopyroxenite characterized the rest of the hole to EOH at 152.10 m. The hole was generally barren.

Hole 08-264 was drilled 360 m south of hole 08-254 near-normal to the interpreted dip angle of geology and mineralization, and collared in a steep-faced outcrop exposure. The hole was drilled for the purposes of confirming the current geological model of the Horsetrail Zone as well as for a possible adit for bulk-sampling purposes. The hole collared in weakly mineralized tremolite- and serpentine-altered wehrlite with minor olivine clinopyroxenite to 36.85 m. Variably tremolite- and serpentine-altered dunite was intersected to 86.70 m, followed by nearly unaltered dunite to 165.95 m. This intersection is characterized by moderate to strong sulphide mineralization, with a total average of 0.279 % sulphide Ni over 128 m, including 0.408 % sulphide Ni and 1.19 g/t Pt+Pd over 32 m. The unit is preceded by a zone of intense serpentinization to 182.25 m caused by a fault from 171.80 to 173.85 m. This intersection graded 0.341 % sulphide Ni over 20 m. A moderately mineralized mix of serpentine- and tremolite-altered dunite, tremolite altered clinopyroxenite, and a fault was intersected to 203.50 m. This interval grades 0.223 % sulphide Ni and 1.43 g/t Pt+Pd over 20 m. Dominantly tremolite-altered dunite, with some green dunite, was intersected to EOH at 245.05 m, and was unmineralized to weakly mineralized. Hole 08-264 was successful at confirming the geological model of the Horsetrail Zone.

CONCLUSIONS

Holes 08-249 to 08-253 were drilled in the Cliff Zone, in the far eastern part of the intrusive suite, to find new mineralization and to test for possible along strike and down dip extensions of mineralization intersected in holes 07-237 to 07-239. Drilling results were mixed. Hole 08-250 intersected nearly barren dunite, despite its proximity (100 m NW) to the 2007 holes, which may be the result of a fault between holes 07-237 to 07-239 and 08-250. The lack of mineralization in

hole 08-253, to the south of the 2007 holes, most likely reflects the gently dipping nature of the previously encountered mineralization and geology. However, this interpretation is only preliminary; more drilling is needed to confirm or disprove this hypothesis. Hole 08-249 was exceptional in that it intersected mineralization fairly similar to the 2007 holes and it is located approximately 100 m to the southeast. A correlation between this hole and the 2007 holes may be possible, but further drilling is required. The presence of moderate-grade PGE mineralization with sulphide Ni (and Cu) in more than one area of the Cliff Zone is very encouraging and warrants further testing.

Holes 08-254 to 08-261 and 08-264 were drilled in the Horsetrail Zone where a large portion of the current resource at Turnagain is located. These holes collared in a variety of locations, but many were drilled in the area of the proposed starter pit (5 year pit), and drilled to the depth of the designed bottom of either this pit or the 15 year pit. Previous drilling in the Horsetrail Zone, while extensive, was lacking in a few key areas. The 2008 holes were drilled with the purpose of infilling gaps in the current resource, upgrading areas of inferred resource to the indicated category, and upgrading some indicated to the measured category. An additional purpose of these infill holes was to further define high-grade mineralization that was intersected in previous drilling. With the exception of hole 08-257, these infill holes intersected high-grade mineralization over significant widths at varying depths and confirmed previously intersected high-grade zones. Although it is not known how this definition of high-grade mineralization will affect the resource, the infill program succeeded in filling many of the gaps that previously existed in the Horsetrail Zone. Hole 08-264, with the purpose of confirming mineralization and geology in the hopes of determining an appropriate location for an adit for bulk-sampling, was exceptional in many ways. Not only was it drilled at -5 degrees, normal to interpreted geology and mineralization, but it was drilled into the centre of the Horsetrail Zone through previously intersected high grade mineralization. This hole confirmed that the current geological model of the Horsetrail Zone is correct, and that the extensive high grade mineralization located within the Horsetrail Zone is in fact continuous.

RECOMMENDATIONS

The holes described in this report succeeded in confirming and better defining high grade areas, and filling in gaps in the inferred and indicated resources, within the Horsetrail Zone, as well as intersecting new mineralization or possible continuity to previously intersected mineralization in the Cliff Zone. Definition and infill drilling in the Northwest Zone would also be beneficial for resource-upgrading purposes. Further drilling in the Cliff Zone, at a minimum of 50 m centres, would better define and expand the Ni+PGE mineralization. Due to the higher variability of PGE mineralization compared to Ni mineralization in the Cliff Zone, a tighter spacing would be better suited to PGE resource definition.

REFERENCES

- Baldys, C. and Hitchins, A. (2004): Turnagain Nickel Property Diamond Drill Report on Cub Claim, BC Ministry of Energy and Mines Assessment Report 27341.
- Brown, D. H. (1978): Assessment Report on Diamond Drilling, Nickel-Star Property, BC Ministry of Energy and Mines Assessment Report 6725.
- Burgoyne, Alfred A. (1971): Geochemical Soil Survey, Agnes and Sand Mineral Claims, Liard Mining Division, BC Ministry of Energy and Mines Assessment Report 3206.
- Clark, Thomas (1980): Petrology of the Turnagain Ultramafic Complex, Northwestern British Columbia, Canadian Journal of Earth Sciences, vol. 17, no.6, pp. 744-757.
- Cukor, V. (1980): Cub Mineral Claim, Turnagain River Area, Liard Mining Division, BC Ministry of Energy and Mines Assessment Report 8055.
- Cukor, V. (1987): Geological Report on the Cub Claims, Liard Mining Division, BC Ministry of Energy and Mines Assessment Report 16458.
- Downing, B. (1998): Turnagain Nickel-Cobalt Project, BC Ministry of Energy and Mines Assessment Report 25475.
- Downing, B. (2003): Report on Turnagain Nickel, Cobalt, Copper, PGM Project, BC Ministry of Energy and Mines Assessment Report 27119.
- Gabrielse, H. (1998): Geology of Cry Lake and Dease Lake Map Areas, North Central British Columbia, Geological Survey of Canada Bulletin 504.
- Livgard, E. (1996): Exploration 1996, Cub Claims, Liard Mining Division, BC Ministry of Energy and Mines Assessment Report 24911.
- McDougall, J.J. and Clark, T. (1972): Geological Report on the South Group Mineral Claims, Turnagain River, BC, BC Ministry of Energy and Mines Assessment Report 3735.
- McDougall, J.J. and Clark, T. (1973): Geological Report on the North Group Mineral Claims, Turnagain River, BC, BC Ministry of Energy and Mines Assessment Report 4097.
- Nixon, G.T. (1998): Ni-Cu Mineralization in the Turnagain Alaskan-type Complex: A Unique Magmatic Environment in Geological Fieldwork 1997, pp. 18-1 to 18-10.
- Page, Jay W. (1986): Report on a Geochemical Survey on the Turnagain Property, Liard Mining Division, BC Ministry of Energy and Mines Assessment Report 15994.
- Scheel, J.E. (2007): Age and Origin of the Turnagain Alaskan-type Intrusion and Associated Ni-Sulphide Mineralization, North-Central British Columbia, Canada; unpublished M.Sc. thesis, *University of British Columbia*, 210 p.
- Woods, D.V. and Downing, B. (2003): Geophysical Interpretation Report on Magnetic and Induced Polarization-Resistivity Surveys, BC Ministry of Energy and Mines Assessment Report 27119.

Appendix A

Claims List

Tenure Number	Claim Name	Area	Good To Date
407627	PUP 4	500.0	2019/jan/01
501131	Drift 1	421.965	2019/jan/12
501168	Drift 2	421.755	2019/jan/12
501234	Drift 3	421.729	2019/jan/12
501298	Drift 4	421.794	2019/jan/12
503365		793.347	2019/feb/18
508218	Dinah 1	407.204	2019/mar/03
508219	Dinah 2	407.052	2019/mar/03
508221	Dinah 3	406.859	2019/mar/03
508222	Dinah 4	406.701	2019/mar/03
508223	Dinah 5	407.096	2019/mar/03
508225	Dinah 6	407.096	2019/mar/03
508226	Dinah 7	254.575	2019/mar/03
508227	Dinah 8	407.298	2019/mar/03
508228	Dinah 9	135.529	2019/mar/03
508229	Dinah 10	203.4	2019/mar/03
510889		1627.862	2019/apr/07
510892		1219.257	2019/apr/07
510910		1424.279	2019/apr/07
510911		1066.865	2019/apr/07
510912		779.891	2019/apr/07
511214		979.883	2019/feb/18
511226		1216.076	2019/feb/18
511227		506.714	2019/feb/17
511230		760.466	2019/feb/17
511234		185.888	2019/feb/16
511244		489.918	2019/feb/18
511251		473.406	2019/feb/17
511257		1014.444	2019/feb/17
511279		896.687	2019/feb/17
511304		1149.679	2019/feb/17
511305		270.959	2019/sep/27
511306		881.166	2019/feb/19
511329		1015.364	2019/sep/27
511330		592.594	2018/dec/01
511337		1065.752	2018/dec/01
511340		253.92	2018/dec/01
511344		270.999	2019/feb/19
511347		474.339	2019/apr/07
511348		389.388	2018/dec/01

Tenure Number	Claim Name	Area	Good To Date
511586		236.94	2019/jan/01
511593		101.549	2019/jan/01
511627		592.115	2018/dec/01
511628		708.952	2019/feb/18
511629		472.918	2019/feb/18
528780	T1	67.745	2019/feb/23
528781	T2	203.314	2019/feb/23
528782	T3	152.557	2019/feb/23
528784	T4	288.253	2019/feb/23
528787	T5	169.649	2019/feb/23
528788	T6	270.22	2019/feb/23
528789	T7	422.475	2019/feb/23
528790	T8	253.607	2019/feb/23
570454		456.79	2019/may/26
570455		236.961	2019/may/26
570456		220.172	2019/may/26
570457		16.93	2019/may/26

Expiry dates are conditional upon the acceptance of this assessment report.

Appendix B

DRILL LOG LEGEND

Sample Data

- depths in metres
- sample numbers correlate with analytical sheets

Sulphide Summary

- visual estimates in percent

Mineralogy and Description

- dominant rock forming mineral identified
- content and other minerals and alterations designated

Symbol	Definition
alt	altered (undetermined)
B	blank
b	broken
bk	black
bn	brown
bt	biotite
bx	breccia
c	competent
ca	calcite
cb	carbonate
chl	chlorite, chloritic
chy	chrysotile
cpx	clinopyroxene
cPx	clinopyroxenite
cpy	chalcopyrite
CS	calc-silicate
D	duplicate
Di	diorite
Dk	dyke
Du	dunite
ep	epidote
f	fractured
Flt	fault
fs	feldspar, feldspathic
gDu	green dunite
gn	green
gr	graphite, graphitic
GS	graphite-sulphide
gt	garnet
gy	grey
hb	hornblende
Hb	hornblendite

Symbol	Definition
Hfs	hornfels
I	intense
lt	light
M	moderate
ma	magnesite
md	medium
MSD	metasediment
mt	magnetite
N	none
ocPx	olivine clinopyroxenite
ol	olivine
or	orange
Phy	phyllite
pk	pink
pn	pentlandite
po	pyrrhotite
py	pyrite
qtz	quartz
si	silica, siliceous
sh	sheared
sp	serpentine, serpenitimized
Sp	serpentinite
STD	standard
tl	talc
tr	tremolite
UM	ultramafic
va	valleriite
W	weak
Wh	wehrlite
wt	white
/45	angle to core axis
/-1	no preferred angle

Hole 08-249

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	temoite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
			646101	STD																			
08-249	0.00	3.05																					
08-249	3.05	26.00			0.05	0.00	0.05	0.00	0.05	va-0.05	ol	W	N	N	W	M	N	N		gy	Wh	sp,mt	c/-1,f/60
08-249	3.05	4.00	646102																				
08-249	4.00	8.00	646103																				
08-249	8.00	12.00	646104																				
08-249	12.00	16.00	646105																				
08-249	16.00	20.00	646106																				
08-249	20.00	24.00	646107																				
08-249	24.00	28.00	646108																				
08-249	26.00	41.20			0.05	0.00	0.05	0.00	0.00	0.00	ol	M	N	N	M	M	N	N		dkgy	sptrDu	sp,tr	c/-1,f/45
08-249	28.00	32.00	646109																				
			646110	B																			
08-249	32.00	36.00	646111																				
08-249	36.00	40.00	646112																				
08-249	40.00	41.20	646113																				
08-249	41.20	43.75			5.00	0.00	5.00	0.50	0.00	0.00	sp	I	N	N	M	I	N	N		dkgy	sptrDu	sp,tr	c/-1
08-249	41.20	44.00	646114																				
08-249	43.75	46.70			0.05	0.05	0.05	0.00	0.00	0.00	sp	M	N	N	M	M	N	N	ep	dkgy,bngn	sptrDu,altDk	sp,ep	f/60
08-249	44.00	48.00	646115																				
08-249	46.70	55.10			0.00	0.00	0.00	0.00	0.00	0.00	sp	M	N	N	M	I	N	N		gy	trspDu	tr,sp	c/-1
08-249	48.00	52.00	646116																				
08-249	52.00	56.00	646117																				
08-249	55.10	58.10			4.00	0.00	4.00	0.40	0.00	0.00	ol	I	N	N	M	I	N	N		dkgy	sptrDu	sp,tr	c/-1,f/60
08-249	56.00	58.10	646118																				
08-249	58.10	59.50			0.05	0.00	0.05	0.00	0.00	0.00	cpx	W	N	N	M	W	N	N		ltgy	trocPx	tr	sh/30
08-249	58.10	60.00	646119																				
08-249	59.50	68.90			0.50	0.00	0.50	0.05	0.00	0.00	ol	M	N	N	M	M	N	N		mdgy	trspDu	tr,bksp	f/60,c/-1
08-249	60.00	64.00	646120																				
08-249	64.00	68.00	646121																				
08-249	68.00	72.00	646122																				
08-249	68.90	77.80			0.10	0.00	0.10	0.05	0.00	0.00	ol	M	N	N	M	M	N	N		mdgy	trspDu	tr,sp	c/-1
08-249	72.00	76.00	646123																				
08-249	76.00	80.00	646124																				
			646125	STD																			

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/bf/sh/FLT
			646126	STD																			
08-249	77.80	87.80			1.00	0.05	1.00	0.10	0.00	0.00	sp	I	N	N	M	I	N	N		dkgy	sptrDu	bksp,tr	c/-1,f/60
08-249	80.00	84.00	646127																				
08-249	84.00	88.00	646128																				
08-249	87.80	90.30			0.20	0.30	0.50	0.05	0.00	0.00	sp	I	N	N	M	I	N	N		dkgy	sptrDu	bksp,tr	f/45
08-249	88.00	90.30	646129																				
08-249	90.30	92.20			0.20	0.20	0.40	0.05	0.00	0.00	sp	I	N	N	M	I	N	W		dkgy,gnwt	sptrWh,CS	bksp,tr	f/55
08-249	90.30	92.00	646130	D																			
08-249	92.00	96.00	646131																				
08-249	92.20	96.65			2.50	2.50	5.00	0.05	0.05	0.00	sp	I	N	N	M	I	N	W		dkgy	sptrDu	bksp,tr	sh/45
08-249	96.00	100.00	646132																				
08-249	96.65	100.90			2.00	8.00	10.00	0.05	0.00	0.00	sp	I	N	N	M	I	N	M		dkgy	sptrDu,MGS	bksp,tr	sh/45
08-249	100.00	104.00	646133																				
08-249	100.90	107.00			1.00	2.00	3.00	0.05	0.00	0.00	sp	I	N	N	M	M	N	W		dkgy	sptrDu	bksp,tr	c/-1,sh/50
08-249	104.00	107.00	646134																				
08-249	107.00	111.10			0.10	0.00	0.10	0.00	0.00	0.00	cpx	M	N	N	W	M	N	N		gngy	ocPx	sp,tr	sh/45
08-249	107.00	108.00	646135																				
08-249	108.00	111.10	646136																				
08-249	111.10	121.40			0.50	0.05	0.50	0.05	0.00	0.00	ol	M	N	N	M	I	N	N		mdgy	trspDu	tr,sp	f/45
08-249	111.10	112.00	646137																				
08-249	112.00	116.00	646138																				
08-249	116.00	120.00	646139																				
			646140	B																			
08-249	120.00	124.00	646141																				
08-249	121.40	133.55			1.00	0.05	1.00	0.10	0.00	0.00	ol	M	W	N	M	I	N	N		mdgy	trspDu	tr,sp	c/-1,f/30
08-249	124.00	128.00	646142																				
08-249	128.00	132.00	646143																				
08-249	132.00	136.00	646144																				
08-249	133.55	135.00			0.05	0.10	0.10	0.00	0.05	0.00	sp	I	M	N	W	I	N	N		dkgy,gn	spDu,altDk	sp,ma	sh/45
08-249	135.00	144.25			1.00	0.10	1.10	0.10	0.00	0.00	ol	M	N	N	M	I	N	N		dkgy,mdgy	trspDu	tr,sp	c/-1,f/60
08-249	136.00	140.00	646145																				
08-249	140.00	144.00	646146																				
08-249	144.00	148.00	646147																				
08-249	144.25	149.50			3.00	1.00	4.00	0.50	0.05	0.00	cpx	M	N	N	M	M	N	N		ltgy,dkgy	trcPx,trspWh	tr,sp	f/60
08-249	148.00	149.50	646148																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/bf/sh/FLT
08-249	149.50	150.60			0.00	0.05	0.05	0.00	0.00	0.00	hb	W	N	N	W	N	N	N	ep,chl	dkgy	altDk	ep,chl	f/50
08-249	149.50	150.60	646149																				
			646150	STD																			
			646151	STD																			
08-249	150.60	160.90			2.00	0.10	2.10	0.20	0.00	0.00	ol	M	N	N	M	I	N	N		dkgy	sptrDu	bksp,tr	c/-1
08-249	150.60	152.00	646152																				
08-249	152.00	156.00	646153																				
08-249	156.00	160.00	646154																				
08-249	160.00	164.00	646155																				
08-249	160.90	164.45			2.00	4.00	6.00	0.50	0.05	0.00	sp	I	N	N	M	I	N	N		dkgy	sptrDu	bksp,tr	c/-1
08-249	164.00	168.00	646156																				
08-249	164.45	167.80			0.30	0.70	1.00	0.05	0.00	0.00	sp	I	N	N	M	I	N	N		dkgy	sptrWh	bksp,tr	c/-1
08-249	167.80	170.00			2.00	8.00	10.00	0.50	0.30	0.00	cpx	M	N	N	W	M	N	N	chl	bngy	altcPx	bksp,chl	f/30
08-249	168.00	170.00	646157																				
08-249	170.00	172.90			0.30	0.05	0.30	0.05	0.00	0.00	ol	M	N	N	M	I	N	N		dkgy	trspDu	tr,bksp	f/30
08-249	170.00	172.00	646158																				
08-249	172.00	174.15	646159																				
08-249	172.90	174.15			0.50	5.00	5.50	0.00	0.05	0.00	cpx	M	W	N	W	M	N	N		gygn	altcPx	bksp	sh/20,f/50
08-249	174.15	183.50			0.20	7.00	7.20	0.20	0.05	0.00	sp	I	W	N	M	I	N	W		dkgy	sptrDu	bksp,tr	sh/45
08-249	174.15	176.00	646160	D																			
08-249	176.00	180.00	646161																				
08-249	180.00	184.00	646162																				
08-249	183.50	188.40			3.00	0.00	5.00	0.10	0.00	0.00	ol	M	N	N	M	I	N	N		dkgy	trspDu	tr,bksp	c/-1,f/60
08-249	184.00	188.00	646163																				
08-249	188.00	192.00	646164																				
08-249	188.40	199.10			4.00	2.00	6.00	0.10	0.20	0.00	sp	I	W	N	M	I	N	N		dkgy	sptrDu	bksp,tr	sh/60
08-249	192.00	196.00	646165																				
08-249	196.00	200.00	646166																				
08-249	199.10	211.65			2.00	1.00	3.00	0.20	0.00	0.00	ol	M	N	N	M	I	N	N		mdgy	trspDu	tr,bksp	c/-1
08-249	200.00	204.00	646167																				
08-249	204.00	208.00	646168																				
08-249	208.00	212.00	646169																				
08-249	211.65	220.10			0.20	0.00	0.20	0.05	0.00	0.00	tr	W	N	N	M	I	N	N		mdgy	trspDu	tr,bksp	c/-1
08-249	212.00	216.00	646170																				
08-249	216.00	220.00	646171																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-249	220.00	224.00	646172																				
08-249	220.10	227.15			2.00	2.00	4.00	0.10	0.00	0.00	ol	M	N	N	M	I	N	N		dkgy	trspDu	tr,bksp	c/-1,f/30
08-249	224.00	228.00	646173																				
08-249	227.15	232.20			0.00	0.00	0.00	0.00	0.00	0.00	cpx	M	N	N	M	M	N	N		dkgy,gy	trspDu,trcPx	tr,bksp	c/-1
08-249	228.00	232.00	646174																				
			646175	STD																			
			646176	STD																			
08-249	232.00	236.00	646177																				
08-249	232.20	235.75			0.05	0.05	0.05	0.00	0.05	0.00	cpx	M	N	N	M	W	N	N		ltgy	trcPx	tr	f/45
08-249	235.75	238.20			0.05	0.00	0.05	0.00	0.00	0.00	ol	M	N	N	M	I	N	N		dkgy	trspDu	tr,bksp	f/50
08-249	236.00	238.20	646178																				
08-249	238.20	249.70			2.00	0.50	2.50	0.20	0.20	0.00	ol	M	N	N	M	I	N	N		dkgy	trspDu	tr,bksp	c/-1,f/60
08-249	238.20	240.00	646179																				
			646180	B																			
08-249	240.00	244.00	646181																				
08-249	244.00	248.00	646182																				
08-249	248.00	249.70	646183																				
08-249	249.70	265.65			0.10	1.00	1.10	0.05	0.05	0.00	ol	M	N	N	M	M	N	N		gy	alltrcPx,trspWh	tr,bksp	f/60
08-249	249.70	252.00	646184																				
08-249	252.00	256.00	646185																				
08-249	256.00	260.00	646186																				
08-249	260.00	264.00	646187																				
08-249	264.00	268.00	646188																				
08-249	265.65	271.30			1.50	0.05	1.50	0.05	0.00	0.00	ol	W	N	N	M	I	N	N		gy	trspDu	tr,bksp	c/-1
08-249	268.00	272.00	646189																				
08-249	271.30	274.20			1.00	1.50	2.50	0.05	0.00	0.00	ol	M	N	N	M	I	N	N		dkgy	sptrDu	bksp,tr	c/-1
08-249	272.00	276.00	646190	D																			
08-249	274.20	300.85			2.00	0.00	2.00	0.05	0.00	0.00	ol	M	N	N	M	I	N	N		dkgy	trspDu	tr,bksp	f/45,c/-1
08-249	276.00	280.00	646191																				
08-249	280.00	284.00	646192																				
08-249	284.00	288.00	646193																				
08-249	288.00	292.00	646194																				
08-249	292.00	296.00	646195																				
08-249	296.00	300.00	646196																				
08-249	300.00	304.00	646197																				

SAMPLE DATA					SULPHIDES						SIL	MINERALOGY							GEOLOGY				
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FLT
08-249	300.85	308.75			3.00	0.05	3.00	0.10	0.00	0.00	sp	I	W	N	M	I	N	N		dkgy	sptrWh	bksp,tr	f/40
08-249	304.00	308.00	646198																				
08-249	308.00	312.00	646199																				
			646200	STD																			
			646201	STD																			
08-249	308.75	317.30			2.00	0.50	2.50	0.10	0.00	0.00	ol	M	N	N	M	M	N	N		dkgy	trspDu	tr,bksp	f/40,f/70
08-249	312.00	316.00	646202																				
08-249	316.00	320.00	646203																				
08-249	317.30	323.50			2.50	0.50	3.00	0.10	0.00	0.00	sp	I	W	N	M	M	N	N		dkgy	sptrDu	bksp,tr	f/40
08-249	320.00	324.00	646204																				
08-249	323.50	329.25			0.75	0.25	1.00	0.05	0.00	0.00	ol	M	W	N	M	M	N	N	ca	dkgy	trspDu	tr,bksp	f/45
08-249	324.00	328.00	646205																				
08-249	328.00	329.25	646206																				
08-249	329.25	334.05			0.00	0.05	0.05	0.00	0.00	0.00	sp	M	W	W	W	N	N	N	ma	dkgy,gn	spmaDu	sp,ma	f/40
08-249	329.25	332.00	646207																				
08-249	332.00	336.00	646208																				
08-249	334.05	343.00			0.00	1.50	1.50	0.00	0.05	0.00	ma	W	W	M	W	N	N	N	ma	gywt	matlUM	ma,tl	sh/70,c/-1
08-249	336.00	340.00	646209																				
			646210	B																			
08-249	340.00	344.00	646211																				
08-249	343.00	348.20			0.00	2.00	2.00	0.00	0.10	0.00	sp	W	M	W	W	N	N	N	ma,ca	gngy	caUM	ca,sp	c/-1,sh/60
08-249	344.00	348.00	646212																				
08-249	348.00	349.90	646213																				
08-249	348.20	349.90			0.00	0.05	0.05	0.00	0.00	0.00	tl	W	W	I	N	N	N	N		ltgy	tlFlt	tl	sh/60
08-249	349.90	355.20			0.00	3.00	3.00	0.00	0.10	py-2.0	tl	W	W	I	N	N	N	N		ltgy	MSD	qtz	f/40
08-249	349.90	352.00	646214																				
08-249	352.00	356.00	646215																				
08-249	355.20	356.10			0.00	0.00	0.00	0.00	0.00	0.00	qtz	N	N	N	N	N	N	W	qtz	dkgy	grFlt	qtz	f/-1
08-249	356.00	360.00	646216																				
08-249	356.10	358.00			0.00	2.00	2.00	0.00	0.05	py-2.0	qtz	N	N	N	N	N	N	M	qtz	bngy	MSD	qtz	f/30
08-249	358.00	361.20			0.00	0.20	0.20	0.00	0.00	py-0.2	qtz	N	N	N	N	N	N	I	qtz	dkgy	Flt	qtz	sh/-1
08-249	361.20	370.35			0.00	1.00	1.00	0.00	0.00	py-0.7	qtz	N	N	N	N	N	N	I	qtz	dkgy	Phy	qtz	sh/60

Hole 08-250

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FLT
08-250	0.00	3.05																					
08-250	3.05	12.80			0.00	0.00	0.00	0.00	0.00	0.00	sp	M	M	N	W	M	N	N	ca	gy.gn	Flt	sp	sh/65,sh/10
08-250	3.05	8.00	646217																				
08-250	8.00	12.00	646218																				
08-250	12.00	16.00	646219																				
08-250	12.80	66.35			0.00	0.00	0.00	0.00	0.00	0.00	ol	W	N	N	M	I	N	N		ltgy	trspDu	tr,bksp	f/65,f/30
08-250	16.00	20.00	646220	D																			
08-250	20.00	24.00	646221																				
08-250	24.00	28.00	646222																				
08-250	28.00	32.00	646223																				
08-250	32.00	36.00	646224																				
			646225	STD																			
			646226	STD																			
08-250	36.00	40.00	646227																				
08-250	40.00	44.00	646228																				
08-250	44.00	48.00	646229																				
08-250	48.00	52.00	646230																				
08-250	52.00	56.00	646231																				
08-250	56.00	60.00	646232																				
08-250	60.00	64.00	646233																				
08-250	64.00	68.00	646234																				
08-250	66.35	166.50			0.00	0.05	0.05	0.00	0.00	0.00	ol	W	N	N	M	I	N	N		ltgy	trspDu	tr,bksp	f/65,c/-1
08-250	68.00	72.00	646235																				
08-250	72.00	76.00	646236																				
08-250	76.00	80.00	646237																				
08-250	80.00	84.00	646238																				
08-250	84.00	88.00	646239																				
			646240	B																			
08-250	88.00	92.00	646241																				
08-250	92.00	96.00	646242																				
08-250	96.00	100.00	646243																				
08-250	100.00	104.00	646244																				
08-250	104.00	108.00	646245																				
08-250	108.00	112.00	646246																				
08-250	112.00	116.00	646247																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	temoite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FLT
08-250	116.00	120.00	646248																				
08-250	120.00	124.00	646249																				
			646250	STD																			
			646251	STD																			
08-250	124.00	128.00	646252																				
08-250	128.00	132.00	646253																				
08-250	132.00	136.00	646254																				
08-250	136.00	140.00	646255																				
08-250	140.00	144.00	646256																				
08-250	144.00	148.00	646257																				
08-250	148.00	152.00	646258																				
08-250	152.00	156.00	646259																				
08-250	156.00	160.00	646260																				
08-250	160.00	164.00	646261																				
08-250	164.00	168.00	646262																				
08-250	166.50	181.95			0.00	0.05	0.05	0.00	0.00	0.00	ol	M	W	N	M	I	N	N		dkgy	sptrDu	bksp,tr	f/65
08-250	168.00	172.00	646263																				
08-250	172.00	176.00	646264																				
08-250	176.00	180.00	646265																				
08-250	180.00	181.95	646266																				

Hole 08-251

No Core

Hole 08-252

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	temoite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FLT
08-252	0.00	4.55																					
08-252	4.55	9.85			0.05	0.00	0.05	0.05	0.00	0.00	ol	M	W	N	M	M	N	N		mdgy	trspDu	tr,bksp	f/60
08-252	4.55	8.00	646267																				
08-252	8.00	12.00	646268																				
08-252	9.85	16.55			3.00	0.05	3.00	0.30	0.00	0.00	ol	M	N	N	M	M	N	N		mdgy	sptrDu	bksp,tr	c/-1
08-252	12.00	16.00	646269																				
			646270	B																			
08-252	16.00	20.00	646271																				
08-252	16.55	44.60			0.10	0.00	0.10	0.05	0.00	0.00	ol	W	N	N	M	I	N	N		ltgy	trspDu	tr,bksp	f/60,c/-1
08-252	20.00	24.00	646272																				
08-252	24.00	28.00	646273																				
08-252	28.00	32.00	646274																				
			646275	STD																			
			646276	STD																			
08-252	32.00	36.00	646277																				
08-252	36.00	40.00	646278																				
08-252	40.00	44.00	646279																				
08-252	44.00	48.00	646280	D																			
08-252	44.60	65.55			0.10	0.00	0.10	0.05	0.00	0.00	ol	M	N	N	M	I	N	N		mdgy	trspDu	tr,bksp	c/-1
08-252	48.00	52.00	646281																				
08-252	52.00	56.00	646282																				
08-252	56.00	60.00	646283																				
08-252	60.00	64.00	646284																				
08-252	64.00	68.00	646285																				
08-252	65.55	73.30			0.05	0.00	0.05	0.00	0.00	0.00	ol	M	M	W	M	I	N	N	ca	dkgy	sptrDu	sp,tr	sh/45,sh/30
08-252	68.00	72.00	646286																				
08-252	72.00	76.00	646287																				
08-252	73.30	83.65			0.05	0.00	0.05	0.05	0.00	0.00	ol	M	W	W	M	I	N	N		mdgy	trspdu	tr,bksp	f/45,c/-1
08-252	76.00	80.00	646288																				
08-252	80.00	84.00	646289																				
08-252	83.65	89.15			0.05	0.00	0.05	0.00	0.00	0.00	ol	M	M	N	M	M	N	N		mdgy	trspDu	tr,bksp	sh/30,f/45
08-252	84.00	88.00	646290	D																			
08-252	88.00	92.00	646291																				
08-252	89.15	90.45			0.05	0.00	0.05	0.00	0.00	0.00	cpx	W	M	N	W	W	N	N		gngy	cPx	sp	sh/30
08-252	90.45	93.20			0.00	0.00	0.00	0.00	0.00	0.00	ol	M	W	N	M	M	N	N		mdgy	trspDu	tr,bksp	sh/30,f/45

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-252	92.00	96.00	646292																				
08-252	92.00	96.00	646292		0.05	0.00	0.05	0.00	0.00	0.00	ol	W	N	N	M	M	N	N		ltgy	trspDu	tr,bksp	f/60,c/-1
08-252	96.00	100.00	646293																				
08-252	100.00	104.00	646294																				
08-252	104.00	108.00	646295																				
08-252	108.00	112.00	646296																				
08-252	112.00	116.00	646297																				
08-252	116.00	120.00	646298																				
08-252	120.00	124.00	646299																				
			646300	STD																			
			646301	STD																			
08-252	124.00	128.00	646302																				
08-252	126.20	130.30			0.05	0.00	0.05	0.00	0.00	0.00	cpx	W	M	W	W	W	N	N		gngy	trcPx	tr	f/60,sh/15
08-252	128.00	132.00	646303																				
08-252	130.30	131.70			0.05	0.00	0.05	0.00	0.00	0.00	cpx	M	N	N	M	W	N	N		gngy	trocPx	tr,bksp	c/-1
08-252	131.70	134.50			0.10	0.00	0.10	0.00	0.05	0.00	ol	M	N	N	M	W	N	N		gygn	sprWh	bksp,tr	f/60,c/-1
08-252	132.00	136.00	646304																				
08-252	134.50	138.40			0.05	0.00	0.05	0.00	0.00	0.00	cpx	M	N	N	M	W	N	N		ltgn	trcPx	tr	f/55
08-252	136.00	140.00	646305																				
08-252	138.40	141.65			0.05	0.00	0.05	0.00	0.00	0.00	cpx	M	N	N	M	M	N	N		dkgygn	trspcPx,Wh	tr,bksp	f/60
08-252	140.00	144.00	646306																				
08-252	141.65	160.10			0.00	0.00	0.00	0.00	0.00	0.00	ol	M	N	N	M	M	N	N		dkgy	trspDu	tr,bksp	f/60
08-252	144.00	148.00	646307																				
08-252	148.00	152.00	646308																				
08-252	152.00	156.00	646309																				
08-252	156.00	160.00	646310	D																			
08-252	160.00	164.00	646311																				
08-252	160.10	175.60			0.05	0.00	0.05	0.00	0.00	0.00	ol	M	N	N	M	M	N	N		dkgy	trspWh	tr,bksp	f/60,f/30
08-252	168.00	172.00	646313																				
08-252	172.00	176.00	646314																				
08-252	175.60	185.80			0.05	0.00	0.05	0.00	0.00	0.00	ol	M	N	N	M	M	N	N		dkgy	trspDu	tr,bksp	f/30,c/-1
08-252	176.00	180.00	646315																				
08-252	180.00	184.00	646316																				
08-252	184.00	188.00	646317																				
08-252	185.80	187.55			0.10	0.00	0.10	0.00	0.00	0.00	cpx	W	W	N	M	W	N	N		ltgy	altcPx	tr	sh/60

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-252	187.55	190.60			0.05	0.00	0.05	0.00	0.00	0.00	ol	M	N	N	M	M	N	N		dkgy	trspWh	tr,bksp	sh/60,sh/20
08-252	188.00	192.00	646318																				
08-252	190.60	203.60			0.05	0.00	0.05	0.00	0.00	0.00	ol	M	W	N	M	M	N	N	ma	dkgy	trspWh	tr,bksp	sh/60,sh/30
08-252	192.00	196.00	646319																				
08-252	196.00	200.00	646320																				
08-252	200.00	204.00	646321																				
08-252	203.60	214.50			0.10	0.00	0.10	0.05	0.05	0.00	ol	M	M	W	M	M	N	N	ma	dkgy	sptrWh	sp,tr	sh/60,sh/45
08-252	204.00	208.00	646322																				
08-252	208.00	212.00	646323																				
08-252	212.00	214.50	646324																				
			646325	STD																			
			646326	STD																			
08-252	214.50	224.70			0.60	0.10	0.70	0.00	0.05	0.00	ol	M	N	N	I	M	N	N		dkgy	trspWh	tr,bksp	c/-1,f/60
08-252	214.50	216.00	646327																				
08-252	216.00	220.00	646328																				
08-252	220.00	224.00	646329																				
			646330	B																			
08-252	224.00	228.00	646331																				
08-252	224.70	227.40			0.20	0.00	0.20	0.00	0.10	0.00	cpx	W	W	N	M	N	N	N		gngy	trcPx	tr	f/50,sh/35
08-252	227.40	229.85			1.00	0.05	1.00	0.00	0.10	0.00	ol	M	W	N	I	M	N	N		dkgy	trspWh	tr,bksp	c/-1
08-252	228.00	229.85	646332																				
08-252	229.85	234.10			0.50	0.10	0.60	0.05	0.05	0.00	ol	M	M	N	I	M	N	N		dkgy	trspWh	tr,sp	sh/30,sh/60
08-252	229.85	232.00	646333																				
08-252	232.00	236.00	646334																				
08-252	234.10	236.85			4.00	0.00	4.00	0.00	0.05	0.00	ol	M	N	N	I	M	N	N		dkgy	trspWh	tr,bksp	c/-1
08-252	236.00	240.00	646335																				
08-252	236.85	245.35			2.00	0.50	2.50	0.00	0.05	0.00	ol	M	W	N	I	M	N	N	ma	dkgy	trspWh	tr,sp	sh/50,sh/25
08-252	240.00	244.00	646336																				
08-252	244.00	248.00	646337																				
08-252	245.35	248.75			0.00	1.00	1.00	0.00	0.00	0.00	tr	M	N	W	M	N	N	N	ca	bngy	altUM	tr,cb	sh/40,c/-1
08-252	248.00	250.60	646338																				
08-252	248.75	250.60			0.00	0.70	0.70	0.00	0.00	0.00	sp	M	N	M	W	N	N	W		dkgy	altWh	sp,tl	sh/60
08-252	250.60	254.60			0.00	0.70	0.70	0.00	0.00	py-0.3	ca	N	N	W	N	N	N	M	ca,chl	gnbn	MSD	ca,chl	sh/60
08-252	250.60	252.00	646339																				
08-252	252.00	254.60	646340	D																			

Hole 08-253

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FLT
08-253	0.00	6.10																					
08-253	6.10	14.15			0.00	0.00	0.00	0.00	0.00	0.00	ol	M	N	N	I	W	N	N		dkgy	trspWh	tr,bksp	f/60
08-253	6.10	8.00	646341																				
08-253	8.00	12.00	646342																				
08-253	12.00	16.00	646343																				
08-253	14.15	17.80			0.10	0.05	0.10	0.00	0.05	py-0.05	ol	M	N	N	M	W	N	N		dkgy-ltgn	Flt	tr,sp	f/60,f/-1
08-253	16.00	20.00	646344																				
08-253	17.80	30.00			0.10	0.05	0.10	0.05	0.00	0.00	ol	M	N	N	M	M	N	N		dkgy	trspDu	tr,bksp	f/60
08-253	20.00	24.00	646345																				
08-253	24.00	28.00	646346																				
08-253	28.00	32.00	646347																				
08-253	30.00	34.25			0.05	0.10	0.10	0.05	0.00	0.00	ol	M	M	W	M	M	N	N	ca	dkgy-gn	altDu	sp	f/60,f/25
08-253	32.00	36.00	646348																				
08-253	34.25	39.05			3.00	3.00	6.00	0.00	0.05	0.00	cpx	W	N	N	M	W	N	N	ca	ltgy	trocPx	tr	f/60,f/30
08-253	36.00	40.00	646349																				
			646350	STD																			
			646351	STD																			
08-253	39.05	44.30			1.50	2.00	3.50	0.05	0.05	0.00	ol	M	N	W	M	I	N	N		dkgy	trspWhocPx	tr,bksp	f/60,f/35
08-253	40.00	44.00	646352																				
08-253	44.00	48.00	646353																				
08-253	44.30	64.50			3.00	2.00	5.00	0.00	0.05	py-0.1	cpx	W	W	N	M	W	N	W		ltgy-bn	trocPx	tr	f/60,f/30
08-253	48.00	52.00	646354																				
08-253	52.00	56.00	646355																				
08-253	56.00	60.00	646356																				
08-253	60.00	64.00	646357																				
08-253	64.00	68.00	646358																				
08-253	64.50	101.95			2.00	0.00	2.00	0.05	0.00	0.00	ol	M	N	N	M	M	N	N		mdgy	trspWh	tr,bksp	f/60,f/30
08-253	68.00	72.00	646359																				
			646360	B																			
08-253	72.00	76.00	646361																				
08-253	76.00	80.00	646362																				
08-253	80.00	84.00	646363																				
08-253	84.00	88.00	646364																				
08-253	88.00	92.00	646365																				
08-253	92.00	96.00	646366																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	temoite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FLT
08-253	96.00	100.00	646367																				
08-253	100.00	101.95	646368																				
08-253	101.95	108.35			0.10	1.50	1.60	0.00	0.05	py-o.1	cpx	W	W	N	W	M	N	W		ltgygn	trcPx	tr	f/30,f/60
08-253	101.95	104.00	646369																				
08-253	104.00	108.00	646370	D																			
08-253	108.00	112.00	646371																				
08-253	108.35	116.10			0.05	0.10	0.10	0.00	0.05	0.00	hb	W	N	N	M	N	N	N		dkgygn	altDk,trocPx	chl	f/30
08-253	112.00	116.00	646372																				
08-253	116.00	120.00	646373																				
08-253	116.10	122.30			0.05	0.00	0.05	0.00	0.00	0.00	ol	M	W	N	M	W	N	N	ma	dkgy,ltgy	Flt	tr,bksp	f/60,f/30
08-253	120.00	124.00	646374																				
			646375	STD																			
			646376	STD																			
08-253	122.30	129.30			0.10	0.05	0.10	0.05	0.00	0.00	cpx	M	N	N	M	W	N	N		dkgy,ltgy	trspocPx,trcPx	tr,bksp	f/25
08-253	124.00	128.00	646377																				
08-253	128.00	129.30	646378																				
08-253	129.30	144.70			2.50	0.50	3.00	0.05	0.05	0.00	ol	M	N	N	M	N	N	N		mdgy	trspDu	tr,bksp	f/60,c/-1
08-253	129.30	132.00	646379																				
08-253	132.00	136.00	646380																				
08-253	136.00	140.00	646381																				
08-253	140.00	144.00	646382																				
08-253	144.00	148.00	646383																				
08-253	144.70	187.40			0.05	0.00	0.05	0.00	0.00	0.00	ol	W	N	N	M	M	N	N		gy	trspDu	tr,bksp	f/60,c/-1
08-253	148.00	152.00	646384																				
08-253	152.00	156.00	646385																				
08-253	156.00	160.00	646386																				
08-253	160.00	164.00	646387																				
08-253	164.00	168.00	646388																				
08-253	168.00	172.00	646389																				
			646390	B																			
08-253	172.00	176.00	646391																				
08-253	176.00	180.00	646392																				
08-253	180.00	184.00	646393																				
08-253	184.00	188.00	646394																				
08-253	187.40	188.65			0.00	0.00	0.00	0.00	0.00	0.00	sp	M	M	W	W	M	N	N	ma	dkgngy	Flt	sp,ma	f/-1

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	temoite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-253	188.00	192.00	646395																				
08-253	188.65	199.80			0.00	0.00	0.00	0.00	0.00	0.00	ol	M	N	N	M	M	N	N		dkgy	trspDu	tr,bksp	sh/30,f/60
08-253	192.00	196.00	646396																				
08-253	196.00	200.00	646397																				
08-253	199.80	205.60			0.15	0.00	0.15	0.00	0.05	5.00	ol	M	N	N	M	M	N	N		dkgy	trspWh	tr,bksp	sh/30,c/-1
08-253	200.00	204.00	646398																				
08-253	204.00	205.60	646399																				
			646400	STD																			
			646401	STD																			
08-253	205.60	216.65			0.10	0.05	0.10	0.00	0.00	0.00	cpx	W	N	N	M	W	N	N		ltgy	trocPx	tr	f/60,f/25
08-253	205.60	208.00	646402																				
08-253	208.00	212.00	646403																				
08-253	212.00	216.00	646404																				
08-253	216.00	219.00	646405																				
08-253	216.65	219.00			3.00	0.20	3.20	0.00	0.05	0.00	cpx	M	N	N	M	W	N	N		gy	trspocPx	tr,bksp	f/30,f/60
08-253	219.00	222.10			1.00	0.05	1.00	0.00	0.05	0.00	cpx	W	N	N	M	W	N	N		ltgy	trocPx	tr,bksp	c/-1
08-253	219.00	220.00	646406																				
08-253	220.00	222.10	646407																				
08-253	222.10	223.40			2.00	6.00	8.00	0.00	0.10	0.00	cpx	M	N	N	M	W	N	W		dkgy	trspocPx	tr,bksp	c/-1
08-253	222.10	224.00	646408																				
08-253	223.40	225.40			1.00	2.00	3.00	0.00	0.05	0.00	cpx	W	N	N	M	W	N	N		ltgy	trcPx	tr	f/30,f/60
08-253	224.00	228.00	646409																				
			646410	B																			
08-253	225.40	227.40			0.05	0.05	0.05	0.00	0.00	0.00	chl	N	N	N	W	N	N	N	chl	dkgy	altDk,trcPx	chl	f/30
08-253	227.40	229.80			0.05	10.00	10.00	0.00	0.05	py-0.05	tr	W	W	N	W	M	N	W	chl	gygnbn	trchlCpx,MGS	tr,chl	f/30,c/-1
08-253	228.00	229.80	646411																				
08-253	229.80	232.25			2.00	2.00	4.00	0.00	0.05	py-0.05	cpx	W	N	N	M	W	N	N		gngy	trcPx	tr	f/30
08-253	229.80	232.00	646412																				
08-253	232.00	233.45	646413																				
08-253	232.25	233.45			1.00	11.00	12.00	0.00	0.10	0.00	cpx	W	N	N	M	N	N	N	chl	dkgygn	trcPx	tr	f/45
08-253	233.45	236.45			1.00	4.00	5.00	0.00	0.05	0.00	cpx	W	N	N	M	W	N	N		dkgy	trcPx	tr	f/45,f/30
08-253	233.45	236.00	646414																				
08-253	236.00	238.90	646415																				
08-253	236.45	238.90			1.00	12.00	13.00	0.00	0.30	0.00	cpx	M	N	N	M	W	N	W	ma	dkgy	trspocPx	tr,bksp	c/-1,f/45
08-253	238.90	241.80			0.50	0.05	0.50	0.00	0.00	0.00	tr	M	W	N	I	N	N	N	ma	dkgy	trspWh	tr,bksp	f/60

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-253	238.90	240.00	646416																				
08-253	240.00	244.00	646417																				
08-253	241.80	247.55			1.00	0.00	1.00	0.05	0.00	0.00	ol	M	N	N	M	M	N	N	chl	dkgy	sptrDu	bksp,tr	f/60,f/30
08-253	244.00	248.00	646418																				
08-253	247.55	248.40			0.30	0.00	0.30	0.00	0.00	0.00	sp	W	I	W	W	W	N	N		gygn	Flt	sp	b/-1,sh/-1
08-253	248.00	252.00	646419																				
08-253	248.40	251.45			2.00	4.00	6.00	0.00	2.00	0.00	cpx	W	W	N	M	W	N	N	ca	dkgybn	altocPx	tr	f/30
08-253	251.45	255.65			0.05	0.00	0.05	0.00	0.00	0.00	sp	M	M	W	M	M	N	N	ca,ma	dkgy	sptrWh	sp,tr	sh/60,sh/30
08-253	252.00	256.00	646420																				
08-253	255.65	267.50			0.05	0.05	0.05	0.00	0.05	0.00	tr	M	W	N	M	M	N	N	ca,ma	dkgygn	trspWh	tr,sp	f/60,sh/30
08-253	256.00	260.00	646421																				
08-253	260.00	264.00	646422																				
08-253	264.00	268.00	646423																				
08-253	267.50	273.70			0.05	0.00	0.05	0.00	0.00	0.00	tr	M	W	N	M	N	N	N	ca,ma	dkgygn	sptrWh	sp,tr	f/60,sh/30
08-253	268.00	272.00	646424																				
			646425	STD																			
			646426	STD																			
08-253	272.00	273.70	646427																				

Hole 08-254

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-254	0.00	7.05																					
08-254	7.05	30.50			1.00	0.50	1.50	0.20	0.00	0.00	ol	M	W	N	W	W	N	N	ca	mdgy	spDu	sp	c/-1
08-254	7.05	12.00	646428																				
08-254	12.00	16.00	646429																				
08-254	16.00	20.00	646430	D																			
08-254	20.00	24.00	646431																				
08-254	24.00	28.00	646432																				
08-254	28.00	32.00	646433																				
08-254	30.50	46.10			0.50	0.50	1.00	0.10	0.00	0.00	ol	W	W	N	W	W	N	N	ca	gygn	gDu	sp	c/-1
08-254	32.00	36.00	646434																				
08-254	36.00	40.00	646435																				
08-254	40.00	44.00	646436																				
08-254	44.00	48.00	646437																				
08-254	46.10	50.10			0.10	0.10	0.30	0.00	0.00	py-0.1	si	W	W	W	N	N	N	N	ca,chl	ltgngy	MSD	alt	sh/-1
08-254	48.00	52.00	646438																				
08-254	50.10	63.40			0.40	0.10	0.50	0.10	0.00	0.00	ol	M	W	N	N	W	N	N	ca	mdgy	spDu	sp	c/-1
08-254	52.00	56.00	646439																				
			646440	B																			
08-254	56.00	60.00	646441																				
08-254	60.00	64.00	646442																				
08-254	63.40	101.20			0.05	0.05	0.05	0.05	0.00	0.00	ol	W	W	N	N	W	N	N		gygn	gDu	sp	c/-1
08-254	64.00	68.00	646443																				
08-254	68.00	72.00	646444																				
08-254	72.00	76.00	646445																				
08-254	76.00	80.00	646446																				
08-254	80.00	84.00	646447																				
08-254	84.00	88.00	646448																				
08-254	88.00	92.00	646449																				
			646450	STD																			
			646451	STD																			
08-254	92.00	96.00	646452																				
08-254	96.00	100.00	646453																				
08-254	100.00	104.00	646454																				
08-254	101.20	111.25			1.30	0.20	1.50	0.50	0.00	0.00	ol	W	W	W	N	W	N	N		gygn	gDu	sp	c/-1
08-254	104.00	108.00	646455																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/bf/sh/FLT
08-254	108.00	112.00	646456																				
08-254	111.25	114.05			1.00	0.50	1.50	0.30	0.00	0.00	ol	M	W	W	N	W	N	W	ca	mdgy	spDu	sp	sh/-1
08-254	112.00	116.00	646457																				
08-254	114.05	192.00			0.10	0.10	0.20	0.05	0.00	0.00	ol	W	W	W	N	W	N	W	ca,bt	gygn	gDu	sp	c/-1
08-254	116.00	120.00	646458																				
08-254	120.00	124.00	646459																				
08-254	124.00	128.00	646460	D																			
08-254	128.00	132.00	646461																				
08-254	132.00	136.00	646462																				
08-254	136.00	140.00	646463																				
08-254	140.00	144.00	646464																				
08-254	144.00	148.00	646465																				
08-254	148.00	152.00	646466																				
08-254	152.00	156.00	646467																				
08-254	156.00	160.00	646468																				
08-254	160.00	164.00	646469																				
			646470	B																			
08-254	164.00	168.00	646471																				
08-254	168.00	172.00	646472																				
08-254	172.00	176.00	646473																				
08-254	176.00	180.00	646474																				
			646475	STD																			
			646476	STD																			
08-254	180.00	184.00	646477																				
08-254	184.00	188.00	646478																				
08-254	188.00	192.00	646479																				
08-254	192.00	200.15			0.20	0.10	0.30	0.10	0.00	0.00	ol	M	W	W	N	W	N	W	ca,bt	gy	spDu	sp	c/-1
08-254	192.00	196.00	646480																				
08-254	196.00	200.00	646481																				
08-254	200.00	204.00	646482																				
08-254	200.15	206.25			0.10	0.10	0.20	0.05	0.00	0.00	ol	W	W	W	N	W	N	W	ca,bt	gygn	gDu	sp	c/-1
08-254	204.00	208.00	646483																				
08-254	206.25	214.40			0.50	1.00	1.50	0.30	0.00	0.00	ol	M	W	N	W	W	N	N	ca,bt	mdgy	shWh	sp	c/-1
08-254	208.00	212.00	646484																				
08-254	212.00	216.00	646485																				

SAMPLE DATA					SULPHIDES						SIL	MINERALOGY							GEOLOGY				
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/bf/sh/FLT
08-254	214.40	220.60			1.50	1.00	2.50	0.05	0.10	py-0.1	ol	M	W	W	W	W	N	W	ca,bt	mdgy	spWh	sp	c/-1
08-254	216.00	220.00	646486																				
08-254	220.00	224.00	646487																				
08-254	220.60	225.15			0.30	0.10	0.40	0.05	0.05	0.00	ol	M	W	W	W	M	N	W	ca	mdgy	spWh	sp	c/-1
08-254	224.00	228.00	646488																				
08-254	225.15	235.30			2.00	1.00	3.00	0.30	0.05	0.00	ol	M	W	W	N	M	N	W	ca	mdgy	spDu	sp	c/-1
08-254	228.00	232.00	646489																				
08-254	232.00	236.00	646490	D																			
08-254	235.30	253.25			0.90	0.10	1.00	0.10	0.05	0.00	ol	M	W	W	N	W	N	W	ca	md-dkgy	spDu	sp	c/-1
08-254	236.00	240.00	646491																				
08-254	240.00	244.00	646492																				
08-254	244.00	248.00	646493																				
08-254	248.00	252.00	646494																				
08-254	252.00	256.00	646495																				
08-254	253.25	256.00			0.30	0.10	0.40	0.05	0.00	0.00	ol	M	W	W	N	W	N	W	ca	md-dkgy	spDu	sp	c/-1
08-254	256.00	275.10			2.20	0.30	2.50	0.30	0.00	0.00	ol	M	W	W	N	W	N	W	ca	md-dkgy	spDu	sp	c/-1
08-254	256.00	260.00	646496																				
08-254	260.00	264.00	646497																				
08-254	264.00	268.00	646498																				
08-254	268.00	272.00	646499																				
			646500	STD																			
			646501	STD																			
08-254	272.00	276.00	646502																				
08-254	275.10	287.40			1.00	0.10	1.10	0.10	0.00	0.00	ol	M	W	W	N	W	N	W		mdgy	spDu	sp	c/-1
08-254	276.00	280.00	646503																				
08-254	280.00	284.00	646504																				
08-254	284.00	288.00	646505																				
08-254	287.40	293.45			1.50	0.10	1.60	0.30	0.00	0.00	ol	M	W	W	N	M	N	W	ca	mdgy	spDu	sp	c/-1
08-254	288.00	292.00	646506																				
08-254	292.00	296.00	646507																				
08-254	293.45	298.75			1.00	0.10	1.10	0.20	0.00	0.00	ol	M	W	W	N	M	N	W	ca	mdgy	spDu	sp	c/-1,sh/-1
08-254	296.00	300.00	646508																				
08-254	298.75	306.00			0.30	0.10	0.40	0.10	0.00	0.00	ol	M	W	W	N	W	N	W	ca,ma	mdgy	spDu	sp	c/-1
08-254	300.00	304.00	646509																				
08-254	304.00	308.00	646510																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY								GEOLOGY				
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FLT
08-254	306.00	312.20			1.00	0.10	1.00	0.20	0.00	0.00	ol	M	W	W	N	W	N	W	ca,ma	mdgy	spDu,Dks	sp	f/50
08-254	308.00	312.00	646511																				
08-254	312.00	316.00	646512																				
08-254	312.20	318.50			0.50	0.10	0.60	0.10	0.00	0.00	ol	M	W	W	N	W	N	W	ca	mdgy	spDu	sp	c/-1,f/40
08-254	316.00	318.50	646513																				

Hole 08-255

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-255	0.00	6.45																					
08-255	6.45	26.80			0.50	0.05	0.55	0.20	0.00	0.00	ol	M	W	W	N	W	N	W		lt-mdgy	spWh	sp	c/-1,f/60
08-255	6.45	10.00	646514																				
08-255	10.00	14.00	646515																				
08-255	14.00	18.00	646516																				
08-255	18.00	22.00	646517																				
08-255	22.00	26.00	646518																				
08-255	26.00	30.00	646519																				
08-255	26.80	31.40			0.80	0.10	0.90	0.20	0.00	0.00	ol	M	W	W	N	W	N	N		lt-mdgy	spWh	sp	f/55,c/-1
08-255	30.00	34.00	646520	D																			
08-255	31.40	45.05			0.50	0.05	0.55	0.10	0.00	0.00	ol	M	W	W	N	W	N	N		lt-mdgy	spWh	sp	b/65
08-255	34.00	38.00	646521																				
08-255	38.00	42.00	646522																				
08-255	42.00	46.00	646523																				
08-255	45.05	47.75			0.80	0.05	0.85	0.10	0.00	0.00	si	M	W	W	N	W	N	N	chl,ca	ltgy	spDu,DiDk	sp,alt	f/50
08-255	46.00	50.00	646524																				
			646525	STD																			
			646526	STD																			
08-255	47.75	68.50			0.50	0.30	0.80	0.20	0.00	0.00	ol	W	W	N	N	W	N	N	ca	lt-mdgy	Wh	sp	c/-1,f/70
08-255	50.00	54.00	646527																				
08-255	54.00	58.00	646528																				
08-255	58.00	62.00	646529																				
			646530	B																			
08-255	62.00	66.00	646531																				
08-255	66.00	70.00	646532																				
08-255	68.50	76.15			0.05	0.05	0.05	0.05	0.00	0.00	ol	M	W	N	W	W	N	N	ca	mdgy	spWh	sp	c/-1,f/60
08-255	70.00	74.00	646533																				
08-255	74.00	78.00	646534																				
08-255	76.15	111.25			0.05	0.00	0.05	0.05	0.00	0.00	ol	M	W	W	M	W	N	N	ca,bt	mdgy	spDu	sp	f/45,c/-1
08-255	78.00	82.00	646535																				
08-255	82.00	86.00	646536																				
08-255	86.00	90.00	646537																				
08-255	90.00	94.00	646538																				
08-255	94.00	98.00	646539																				
08-255	98.00	102.00	646540																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/bf/sh/FLT
08-255	102.00	106.00	646541																				
08-255	106.00	110.00	646542																				
08-255	110.00	114.00	646543																				
08-255	111.25	125.40			0.20	0.05	0.25	0.05	0.00	0.00	ol	M	W	W	N	W	N	N	ca, bt	mdgy	spDu	sp	c/-1
08-255	114.00	118.00	646544																				
08-255	118.00	122.00	646545																				
08-255	122.00	126.00	646546																				
08-255	125.40	138.00			0.10	0.10	0.20	0.05	0.00	0.00	ol	M	W	W	W	W	N	N	ca	lt-mdgy	spWh	sp	f/35
08-255	126.00	130.00	646547																				
08-255	130.00	134.00	646548																				
08-255	134.00	138.00	646549																				
			646550	STD																			
			646551	STD																			
08-255	138.00	152.35			0.50	0.10	0.60	0.10	0.00	0.00	ol	M	W	W	N	W	N	N	bt	mdgy	spWh	sp	c/-1, f/75
08-255	138.00	142.00	646552																				
08-255	142.00	146.00	646553																				
08-255	146.00	150.00	646554																				
08-255	150.00	154.00	646556																				
08-255	152.35	157.20			1.00	0.10	1.10	0.20	0.00	0.00	ol	M	W	W	W	W	N	N	bt	mdgy	spWh	sp	c/-1
08-255	154.00	158.00	646557																				
08-255	157.20	166.00			0.50	0.05	0.55	0.10	0.00	0.00	ol	M	W	W	M	W	N	N	bt	mdgy	spWh	sp	c/-1, f/50
08-255	158.00	162.00	646558																				
08-255	162.00	166.00	646559																				
			646560	B																			
08-255	166.00	171.70			0.30	0.05	0.35	0.05	0.00	0.00	ol	M	W	W	M	W	N	N	bt	md-ltgy	sptrWh	tr	c/-1, f/40
08-255	166.00	170.00	646561																				
08-255	170.00	174.00	646562																				
08-255	171.70	174.80			2.00	0.10	2.10	0.10	0.00	0.00	ol	M	W	W	M	W	N	N	bt	md-ltgy	sptrWh	tr	c/-1
08-255	174.00	178.00	646563																				
08-255	174.80	191.60			0.30	0.05	0.35	0.05	0.00	0.00	ol	M	W	W	M	W	N	W	ca, bt	mdgy-bk	sptrWh	tr	sh/20
08-255	178.00	182.00	646564																				
08-255	182.00	186.00	646565																				
08-255	186.00	190.00	646566																				
08-255	190.00	194.00	646567																				
08-255	191.60	198.20			0.50	0.05	0.55	0.10	0.00	0.00	ol	M	W	W	W	W	N	W	ca, bt	mdgy	trspWh	sp	f/60

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	temoite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/bf/sh/FLT
08-255	194.00	198.00	646568																				
08-255	198.00	202.00	646569																				
08-255	198.20	210.45			0.10	0.05	0.15	0.05	0.00	0.00	ol	M	W	W	M	W	N	W	ca,bt	md-ltgy-bk	trWh	tr	f/70
08-255	202.00	206.00	646570																				
08-255	206.00	210.00	646571																				
08-255	210.00	214.00	646572																				
08-255	210.45	213.80			3.00	0.10	3.10	0.80	0.00	0.00	ol	M	W	W	M	M	N	W	ca,bt	me-ltgy-bk	trWh	tr	c/-1
08-255	213.80	217.25			1.00	0.10	1.10	0.10	0.00	0.00	ol	M	W	W	M	W	N	W	ca,bt	ltgy-bk	trDu	tr	c/-1
08-255	214.00	218.00	646573																				
08-255	217.25	227.50			3.00	0.50	3.50	0.80	0.00	0.00	ol	M	W	W	M	W	N	W	ca,bt	ltgy-bk	trDu	tr	c/-1
08-255	218.00	222.00	646574																				
			646575	STD																			
			646576	STD																			
08-255	222.00	226.00	646577																				
08-255	226.00	230.00	646578																				
08-255	227.50	228.70			0.30	0.10	0.40	0.05	0.00	0.00	ol	M	W	W	M	W	N	W	ca,bt	ltgy-bk	trDu	tr	c/-1
08-255	228.70	232.60			1.50	0.10	1.60	0.30	0.00	0.00	ol	M	W	W	M	W	N	W	ca,bt	ltgy-bk	trDu	tr	c/-1
08-255	230.00	234.00	646579																				
08-255	232.60	234.05			0.80	0.10	0.90	0.20	0.00	0.00	ol	M	W	W	M	W	N	W	ca,bt	ltgy-bk	trDu	tr	c/-1
08-255	234.00	238.00	646580	D																			
08-255	234.05	235.50			1.40	0.10	1.50	0.20	0.00	0.00	ol	M	W	W	M	W	N	W	ca,bt	ltgy-bk	trDu	tr	c/-1
08-255	235.50	242.70			5.00	0.30	5.30	2.00	0.00	0.00	ol	M	W	W	M	W	N	W	ca,bt	ltgy-bk	trDu	tr	c/-1
08-255	238.00	242.00	646581																				
08-255	242.00	246.00	646582																				
08-255	242.70	249.05			10.00	0.50	1.05	4.00	0.00	0.00	ol	M	W	W	M	W	N	W	ca,bt	ltgy-bk	trDu	tr	c/-1
08-255	246.00	250.00	646583																				
08-255	249.05	251.05			1.00	0.10	1.10	0.20	0.00	0.00	ol	M	W	W	M	W	N	W	ca,bt	ltgy-bk	trDu	tr	c/-1
08-255	250.00	254.00	646584																				
08-255	251.05	252.75			9.00	0.50	9.50	3.00	0.00	0.00	ol	M	W	W	M	W	N	W	ca,bt	ltgy-bk	trDu	tr	c/-1
08-255	252.75	254.65			1.00	0.50	1.50	0.20	0.00	0.00	ol	M	W	W	M	W	N	W	ca,bt	ltgy-bk	trDu	tr	c/-1
08-255	254.00	258.00	646585																				
08-255	254.65	260.05			0.50	0.10	0.60	0.10	0.00	0.00	ol	M	W	W	M	W	N	W	ca,bt	ltgy-bk	trDu	tr	c/-1
08-255	258.00	262.00	646586																				
08-255	260.05	262.70			2.00	0.10	2.10	0.30	0.00	0.00	ol	M	W	W	M	W	N	W	ca,bt	ltgy-bk	trDu	tr	c/-1
08-255	262.00	266.00	646587																				

SAMPLE DATA					SULPHIDES						SIL	MINERALOGY							GEOLOGY				
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/bf/sh/FLT
08-255	262.70	269.65			0.50	0.50	1.00	0.10	0.00	0.00	ol	W	W	W	M	W	N	M	ca,bt	ltgy-bk	trWh,GS	tr	f/30
08-255	266.00	270.00	646588																				
08-255	269.65	270.55			5.00	3.00	8.00	1.50	0.00	0.00	ol	M	W	W	W	M	N	M	ca,bt	mdgy	spDu,GS	sp	f/55
08-255	270.00	274.00	646589																				
			646590	B																			
08-255	270.55	274.35			1.00	0.50	1.50	0.30	0.00	0.00	ol	M	W	W	W	M	N	M	ca,bt	mdgy	spDu,GS	sp	f/40
08-255	274.00	278.00	646591																				
08-255	274.35	277.25			0.80	0.20	1.00	0.30	0.00	0.00	ol	M	W	W	W	M	N	W	ca,bt	mdgy	spDu	sp	f/40
08-255	277.25	281.80			10.00	0.50	10.50	4.00	0.00	0.00	ol	M	W	W	W	M	N	W	ca,bt	mdgy	spDu	sp	c/-1
08-255	278.00	282.00	646592																				
08-255	281.80	289.85			0.50	0.20	0.70	0.10	0.00	0.00	ol	M	W	W	W	M	N	W	ca,bt	mdgy	spDu	sp	c/-1
08-255	282.00	286.00	646593																				
08-255	286.00	290.00	646594																				
08-255	289.85	291.70			0.30	0.50	0.80	0.10	0.00	0.00	cpx	W	W	W	W	M	N	W	ca,bt	ltgy	spocPx	sp	f/50
08-255	290.00	294.00	646595																				
08-255	291.70	295.10			0.30	0.70	1.00	0.30	0.05	0.00	ol	M	W	W	W	M	N	W	bt	mdgy	spDu	sp	f/60
08-255	294.00	298.00	646596																				
08-255	295.10	305.50			0.50	0.50	1.00	0.30	0.05	0.00	ol	M	W	W	W	M	N	W	bt	mdgy	spDu	sp	f/70
08-255	298.00	302.00	646597																				
08-255	302.00	306.00	646598																				
08-255	305.50	307.70			12.00	5.00	17.00	2.00	0.10	0.00	ol	M	W	N	W	M	N	W		mdgy	spDu,GS	sp	c/-1,f/70
08-255	306.00	310.00	646599																				
			646600	STD																			
			646601	STD																			
08-255	307.70	311.75			4.00	5.00	11.00	1.00	0.05	0.00	ol	M	W	N	W	M	N	M		mdgy	spDu,GS	sp	c/-1
08-255	310.00	314.00	646602																				
08-255	311.75	316.85			1.00	3.00	4.00	0.50	0.05	0.00	ol	M	W	N	W	M	N	M		mdgy	spDu	sp	f/30
08-255	314.00	318.00	646603																				
08-255	316.85	317.65			8.00	8.00	16.00	3.00	0.10	0.00	ol	M	W	N	W	M	N	M		mdgy	spDu,GS	sp	c/-1
08-255	317.65	323.15			2.00	0.10	2.10	0.50	0.05	0.00	ol	M	W	W	W	W	N	W	chl	mdgy	spDu,Dks	sp	c/-1,f/60
08-255	318.00	322.00	646604																				
08-255	322.00	326.00	646605																				
08-255	323.15	341.70			0.10	0.10	0.20	0.05	0.05	0.00	ol	M	W	W	N	M	N	W	chl,chy	mdgy	spDu,Dks	sp	f/50
08-255	326.00	330.00	646606																				
08-255	330.00	334.00	646607																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FLT
08-255	334.00	338.00	646608																				
08-255	338.00	342.00	646609																				
08-255	341.70	345.45			3.00	1.00	4.00	1.00	0.05	0.00	ol	M	W	W	N	M	N	W	ca,chl	mdgy	spDu	sp	c/-1,f/45
08-255	342.00	346.00	646610	D																			
08-255	345.45	358.15			0.50	0.20	0.70	0.20	0.05	0.00	ol	M	M	W	N	M	N	W	ca,chl	lt-mdgy	spDu,altDk	sp.alt	sh/70
08-255	346.00	350.00	646611																				
08-255	350.00	354.00	646612																				
08-255	354.00	358.15	646613																				

Hole 08-256

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/bf/sh/FLT
08-256	0.00	5.30																					
08-256	5.30	27.15			0.05	0.00	0.05	0.00	0.00	0.00	ol	W	W	N	N	W	N	N	bt,ca	gy	Du	sp	c/-1,f/60
08-256	5.30	8.00	646614																				
08-256	8.00	12.00	646615																				
08-256	12.00	16.00	646616																				
08-256	16.00	20.00	646617																				
08-256	20.00	24.00	646618																				
08-256	24.00	28.00	646619																				
			646620	B																			
			646621																				
08-256	27.15	28.20			0.10	0.00	0.10	0.00	0.00	0.00	cpx	W	W	N	N	W	N	N	ca	ltgy	ocPx	sp	f/40
08-256	28.20	29.70			0.10	0.05	0.15	0.00	0.00	0.00	ol	W	W	N	N	W	N	N	bt,ca	gy	spWh	sp	f/65
08-256	29.70	30.30			3.50	0.50	4.00	0.05	0.00	0.00	ol	W	W	W	N	W	N	N	bt,ca	mdgy	spWh	sp	f/30
08-256	30.30	37.40			0.40	0.10	0.50	0.05	0.00	0.00	cpx	W	W	N	N	W	N	N	bt,ca	ltgy	ocPx	sp	f/40
08-256	32.00	36.00	646622																				
08-256	36.00	40.00	646623																				
08-256	37.40	45.90			0.30	0.05	0.35	0.05	0.00	0.00	ol	M	W	N	N	W	N	N	bt,ca	mdgy	spDu	sp	c/-1,f/75
08-256	40.00	44.00	646624																				
			646625	STD																			
			646626	STD																			
08-256	44.00	48.00	646627																				
08-256	45.90	53.00			0.30	0.05	0.35	0.05	0.00	0.00	ol	M	M	W	N	W	N	N	bt,ca	mdgy	spDu	sp	sh/45
08-256	48.00	52.00	646628																				
08-256	52.00	56.00	646629																				
08-256	53.00	57.20			0.30	0.05	0.35	0.05	0.00	0.00	ol	W	W	W	N	W	N	N	bt,ca	mdgy	Du	sp	c/-1
08-256	56.00	60.00	646630																				
08-256	57.20	60.55			0.80	0.05	0.85	0.05	0.00	0.00	ol	W	W	W	N	W	N	N	bt,ca	mdgy	Du	sp	c/-1
08-256	60.00	64.00	646631																				
08-256	60.55	72.60			0.30	0.05	0.35	0.05	0.00	0.00	ol	W	M	W	N	W	N	N	bt,ca	mdgy	Du	sp	c/-1
08-256	64.00	68.00	646632																				
08-256	68.00	72.00	646633																				
08-256	72.00	76.00	646634																				
08-256	72.60	77.45			0.20	0.05	0.25	0.05	0.00	0.00	ol	W	M	W	N	W	N	N	bt,ca	md-ltgy	Du	sp	sh/50
08-256	76.00	80.00	646635																				
08-256	77.45	92.75			0.10	0.05	0.15	0.05	0.00	0.00	ol	W	W	N	N	W	N	N	bt,ca	mdgy	Du	sp	c/-1

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-256	80.00	84.00	646636																				
08-256	84.00	88.00	646637																				
08-256	88.00	92.00	646638																				
08-256	92.00	96.00	646639																				
08-256	92.75	97.80			0.50	0.05	0.55	0.10	0.00	0.00	ol	M	M	W	N	M	N	N	bt,ca	mdgy	spDu	sp	sh/-1
08-256	96.00	100.00	646640	D																			
08-256	97.80	148.60			0.10	0.05	0.15	0.05	0.00	0.00	ol	M	W	W	N	W	N	N	bt,ca	mdgy	Du	sp	c/-1,f/40,sh/35
08-256	100.00	104.00	646641																				
08-256	104.00	108.00	646642																				
08-256	108.00	112.00	646643																				
08-256	112.00	116.00	646644																				
08-256	116.00	120.00	646645																				
08-256	120.00	124.00	646646																				
08-256	124.00	128.00	646647																				
08-256	128.00	132.00	646648																				
08-256	132.00	136.00	646649																				
			646650	STD																			
			646651	STD																			
08-256	136.00	140.00	646652																				
08-256	140.00	144.00	646653																				
08-256	144.00	148.00	646654																				
08-256	148.00	152.00	646655																				
08-256	148.60	150.00			1.00	2.00	3.00	0.50	0.00	0.00	ol	M	W	W	N	M	N	W	ca	mdgy	spDu	sp	f/60
08-256	150.00	167.60			2.00	5.00	7.00	0.20	0.50	py-0.5	cpx	W	W	N	W	I	N	W	ca	ltgy	cPx	sp	f/50
08-256	152.00	156.00	646656																				
08-256	156.00	160.00	646657																				
08-256	160.00	164.00	646658																				
08-256	164.00	168.00	646659																				
08-256	167.60	169.30			3.00	1.00	4.00	0.05	0.05	py-0.05	cpx	M	W	N	M	W	N	W	bt,ca	mdgy-bk	trocPx	tr	c/-1,f/45
08-256	168.00	172.00	646660																				
08-256	169.30	181.30			0.10	0.05	0.15	0.05	0.00	py-0.05	cpx	M	W	N	M	W	N	W	bt,ca	mdgy-bk	trocPx	tr	c/-1,f/35
08-256	172.00	176.00	646661																				
08-256	176.00	180.00	646662																				
08-256	180.00	184.00	646663																				
08-256	181.30	187.10			0.50	0.10	0.60	0.10	0.00	0.00	ol	W	W	N	W	W	N	W	bt,ca	gy	trWh	tr	c/-1,b/75

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FLT
08-256	184.00	188.00	646664																				
08-256	187.10	191.75			5.00	1.00	6.00	1.00	0.00	0.00	ol	M	N	N	N	W	N	W	bt	md-dkgy	spWh	sp	b/60
08-256	188.00	192.00	646665																				
08-256	191.75	194.85			8.00	1.00	9.00	2.00	0.00	0.00	ol	I	N	N	N	W	N	W	bt	dkgy	spWh	sp	c/-1
08-256	192.00	196.00	646666																				
08-256	194.85	198.50			20.00	11.00	31.00	5.00	0.00	0.00	ol	I	N	N	N	W	N	W	bt	dkgy	spDu	sp	c/-1
08-256	196.00	200.00	646667																				
08-256	198.50	200.25			10.00	1.00	11.00	3.00	0.00	0.00	ol	I	N	N	N	W	N	W	bt	dkgy	spDu	sp	c/-1
08-256	200.00	204.00	646668																				
08-256	200.25	202.30			1.00	2.00	3.00	0.50	0.05	0.00	ol	M	N	N	N	W	N	W	bt	md-dkgy	spDu	sp	f/35
08-256	202.30	206.75			2.00	0.50	2.50	0.50	0.00	0.00	ol	M	N	N	N	W	N	W	bt	mdgy	spDu	sp	c/-1,f/45
08-256	204.00	208.00	646669																				
08-256	206.75	209.40			0.10	0.10	0.20	0.05	0.00	0.00	ol	W	W	W	N	M	N	W	bt	mdgy	spDu	sp	c/-1,f/50
08-256	208.00	212.00	646670	D																			
08-256	209.40	214.00			0.20	0.10	0.30	0.05	0.00	0.00	ol	W	W	W	N	M	N	W	bt	mdgy	spDu	sp	f/70
08-256	212.00	216.00	646671																				
08-256	214.00	223.00			0.20	0.10	0.30	0.05	0.00	0.00	ol	W	W	W	N	W	N	W	bt	gy	Du	sp	c/-1,f/40
08-256	216.00	220.00	646672																				
08-256	220.00	224.00	646673																				
08-256	223.00	225.50			6.00	1.00	7.00	2.00	0.00	0.00	ol	W	W	W	N	M	N	W	bt	gy	Du	sp	c/-1,f/45
08-256	224.00	228.00	646674																				
			646675	STD																			
			646676	STD																			
08-256	225.50	227.50			9.00	2.00	11.00	3.00	0.10	0.00	ol	W	W	W	N	M	N	W	bt	gy	Du	sp	c/-1
08-256	227.50	229.90			2.00	0.50	2.50	0.50	0.00	0.00	ol	W	W	W	N	M	N	W	bt	gy	Du	sp	c/-1,f/40
08-256	228.00	232.00	646677																				
08-256	229.90	249.30			0.05	0.05	0.05	0.05	0.00	0.00	ol	W	W	W	N	W	N	W	bt	gy	Du	sp	c/-1,f/60
08-256	232.00	236.00	646678																				
08-256	236.00	240.00	646679																				
			646680	B																			
08-256	240.00	244.00	646681																				
08-256	244.00	248.00	646682																				
08-256	248.00	252.00	646683																				
08-256	249.30	259.40			0.05	0.05	0.05	0.05	0.00	0.00	ol	M	W	W	N	M	N	W	bt,ca	mdgy	spDu	sp	c/-1,sh/-1
08-256	252.00	256.00	646684																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-256	256.00	260.00	646685																				
08-256	259.40	266.00			0.20	0.30	0.50	0.05	0.00	va-0.05	ol	M	W	W	N	M	N	W	bt,ca	mdgy	spDu	sp	f/65
08-256	260.00	264.00	646686																				
08-256	264.00	268.00	646687																				
08-256	266.00	272.80			1.50	0.50	2.00	0.05	0.00	va-0.05	ol	I	W	W	N	M	N	I	bt,ca	dkgy	spDu,Flt	sp	ft
08-256	268.00	272.00	646688																				
08-256	272.00	276.00	646689																				
08-256	272.80	274.65			2.50	1.50	4.00	0.05	0.00	va-0.05	ol	I	W	W	N	M	N	I	bt,ca	dkgy	spDu,Flt	sp	ft
08-256	274.65	281.95			0.05	0.05	0.05	0.00	0.00	0.00	si	W	W	M	N	W	W	N	ca	gy,wtgy	altspDu,Dks	alt	b/85
08-256	276.00	280.00	646690																				
08-256	280.00	284.00	646691																				
08-256	281.95	290.45			0.50	0.20	0.70	0.05	0.00	va-0.05	ol	M	W	W	N	W	N	W	bt,ca	mdgy	spDu,Dks	sp	f/70
08-256	284.00	288.00	646692																				
08-256	288.00	292.00	646693																				
08-256	290.45	297.65			0.05	0.05	0.05	0.05	0.00	0.00	ol	W	W	W	N	W	N	W	bt,ca	gy	Du	sp	f/65
08-256	292.00	296.00	646694																				
08-256	296.00	300.00	646695																				
08-256	297.65	301.50			3.00	1.00	4.00	1.00	0.00	0.00	ol	M	W	W	N	W	N	W	bt,ca	gy	Du	sp	c/-1,f/60
08-256	300.00	304.00	646696																				
08-256	301.50	308.70			0.80	0.20	1.00	0.10	0.00	0.00	ol	M	W	W	N	W	N	W	bt,ca	gy	Du	sp	f/65
08-256	304.00	308.00	646697																				
08-256	308.00	312.00	646698																				
08-256	308.70	312.90			0.30	0.10	0.40	0.05	0.00	0.00	ol	M	W	W	N	W	N	W	bt,ca	gy	Du	sp	f/50
08-256	312.00	316.00	646699																				
			646700	STD																			
			646701	STD																			
08-256	312.90	326.00			0.10	0.20	0.30	0.05	0.00	0.00	ol	M	W	W	N	W	N	W	bt,ca	mdgy-gy	Flt	alt	ft
08-256	316.00	320.00	646702																				
08-256	320.00	324.00	646703																				
08-256	324.00	327.65	646704																				
08-256	326.00	327.65			0.10	0.00	0.10	0.00	0.00	va-0.05	ol	I	W	W	N	W	N	M	ca	dkgy	spDu	sp	f/40

Hole 08-257

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-257	0.00	5.55																					
08-257	5.55	35.70			0.50	0.05	0.55	0.10	0.00	0.00	ol	W	W	W	N	W	N	W	ca	gy	Du	sp	f/70
08-257	5.55	8.00	646705																				
08-257	8.00	12.00	646706																				
08-257	12.00	16.00	646707																				
08-257	16.00	20.00	646708																				
08-257	20.00	24.00	646709																				
			646710	B																			
08-257	24.00	28.00	646711																				
08-257	28.00	32.00	646712																				
08-257	32.00	36.00	646713																				
08-257	35.70	44.20			0.20	0.30	0.50	0.10	0.00	0.00	si,ol	W	W	W	N	W	N	W	ca	bngy,bk	altDu,Dks	alt	f/50
08-257	36.00	40.00	646714																				
08-257	40.00	44.00	646715																				
08-257	44.00	48.00	646716																				
08-257	44.20	49.50			0.20	0.40	0.60	0.05	0.00	0.00	ol	M	W	W	N	W	N	W	ca	gy	Du	sp	c/-1,f/55
08-257	48.00	52.00	646717																				
08-257	49.50	64.50			0.10	0.10	0.20	0.05	0.00	0.00	ol	M	W	W	N	W	N	W	ca	gy	Du	sp	c/-1,f/45
08-257	52.00	56.00	646718																				
08-257	56.00	60.00	646719																				
08-257	60.00	64.00	646720																				
08-257	64.00	68.00	646721																				
08-257	64.50	65.90			2.00	1.00	3.00	0.50	0.00	0.00	ol	M	W	W	N	W	N	W	ca	gy	Du	sp	c/-1,f/80
08-257	65.90	76.25			0.30	0.05	0.35	0.05	0.00	0.00	ol	W	W	N	N	W	N	N	ca	gygn	gDu	sp	NR
08-257	68.00	72.00	646722																				
08-257	72.00	76.00	646723																				
08-257	76.00	80.00	646724																				
			646725	STD																			
			646726	STD																			
08-257	76.25	82.90			0.40	0.10	0.50	0.20	0.00	0.00	ol	W	W	N	N	W	N	N	ca	gy	gDu	sp	f/50
08-257	80.00	84.00	646727																				
08-257	82.90	87.10			0.05	0.05	0.05	0.05	0.00	0.00	ol,si	W	M	W	N	W	N	N	ca	gy.gnwt	altDu,Dks	alt	b/-1,sh/-1
08-257	84.00	88.00	646728																				
08-257	87.10	100.35			0.10	0.05	0.15	0.05	0.00	0.00	ol	W	W	W	N	W	N	W	ca	gy	Du	sp	f/70
08-257	88.00	92.00	646729																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-257	92.00	96.00	646730	D																			
08-257	96.00	100.00	646731																				
08-257	100.00	104.00	646732																				
08-257	100.35	107.80			0.30	0.10	0.40	0.10	0.00	0.00	ol	W	W	W	N	W	N	W	ca	gy	Du	sp	c/-1,f/80
08-257	104.00	108.00	646733																				
08-257	107.80	110.05			1.00	0.20	1.20	0.30	0.00	0.00	ol	W	W	N	N	W	N	W	ca	gy	Du	sp	c/-1,f/45
08-257	108.00	112.00	646734																				
08-257	110.05	113.75			0.20	0.05	0.25	0.05	0.00	0.00	ol	W	W	N	N	W	N	W	ca	gy	Du	sp	f/80
08-257	112.00	116.00	646735																				
08-257	113.75	118.85			1.00	0.20	1.20	0.30	0.00	0.00	ol	W	W	N	N	W	N	W	ca	gy	Du	sp	c/-1,f/55
08-257	116.00	120.00	646736																				
08-257	118.85	126.90			0.10	0.05	0.15	0.05	0.00	0.00	ol	W	W	N	N	W	N	W	ca	gy	Du	sp	c/-1,f/55
08-257	120.00	124.00	646737																				
08-257	124.00	128.00	646738																				
08-257	126.90	129.60			0.20	0.10	0.30	0.05	0.00	0.00	ol	W	M	W	N	W	N	N	ca	gy,wt	Flt	sp	ft
08-257	128.00	132.00	646739																				
			646740	B																			
08-257	129.60	146.50			0.10	0.05	0.15	0.05	0.00	0.00	ol	W	W	W	N	W	N	N	ca	gy	Du	sp	f/-1
08-257	132.00	136.00	646741																				
08-257	136.00	140.00	646742																				
08-257	140.00	144.00	646743																				
08-257	144.00	148.00	646744																				
08-257	146.50	178.50			0.05	0.00	0.05	0.05	0.00	0.00	ol	W	W	N	N	W	N	N	bt,ca	gngy	gDu	sp	c/-1,f/60
08-257	148.00	152.00	646745																				
08-257	152.00	156.00	646746																				
08-257	156.00	160.00	646747																				
08-257	160.00	164.00	646748																				
08-257	164.00	168.00	646749																				
			646750	STD																			
			646751	STD																			
08-257	168.00	172.00	646752																				
08-257	172.00	176.00	646753																				
08-257	176.00	180.00	646754																				
08-257	178.50	185.35			0.50	0.10	0.60	0.20	0.00	0.00	ol	M	W	N	N	W	N	N	bt,ca	mdgy	spDu	sp	c/-1
08-257	180.00	184.00	646755																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-257	184.00	188.00	646756																				
08-257	185.35	192.20			1.00	0.10	1.10	0.30	0.00	0.00	ol	M	W	N	N	W	N	N	bt,ca	mdgy	spDu	sp	c/-1
08-257	188.00	192.00	646757																				
08-257	192.00	196.00	646758																				
08-257	192.20	213.90			0.30	0.10	0.40	0.10	0.00	0.00	ol	M	M	W	N	W	N	W	bt,ca	mdgy	spDu	sp	sh/-1,f/50
08-257	196.00	200.00	646759																				
08-257	200.00	204.00	646760	D																			
08-257	204.00	208.00	646761																				
08-257	208.00	212.00	646762																				
08-257	212.00	216.00	646763																				
08-257	213.90	241.00			0.10	0.10	0.20	0.05	0.00	0.00	ol	W	W	W	W	W	N	W	bt,ca	gngy	gDu	sp	f/70
08-257	216.00	220.00	646764																				
08-257	220.00	224.00	646765																				
08-257	224.00	228.00	646766																				
08-257	228.00	232.00	646767																				
08-257	232.00	236.00	646768																				
08-257	236.00	240.00	646769																				
			646770																				
08-257	240.00	244.00	646771																				
08-257	241.00	246.20			0.30	0.20	0.50	0.20	0.00	0.00	ol	W	N	W	M	W	N	N	bt	ltgy	trWh	tr	c/-1,f/85
08-257	244.00	248.00	646772																				
08-257	246.20	248.70			0.60	0.60	1.20	0.30	0.00	0.00	ol	W	W	W	M	W	N	N	bt	ltgy	trWh	tr	f/40
08-257	248.00	252.00	646773																				
08-257	248.70	257.30			0.50	1.00	1.50	0.20	0.00	0.00	ol	W	W	W	M	W	N	N	bt,ca	ltgy	trWh	tr	f/30
08-257	252.00	256.00	646774																				
			646775	STD																			
			646776	STD																			
08-257	256.00	260.00	646777																				
08-257	257.30	273.40			0.30	0.10	0.40	0.10	0.00	0.00	ol	M	W	W	M	W	N	W	bt,ca	gy	trspWh	tr	f/55,sh/-1
08-257	260.00	264.00	646778																				
08-257	264.00	268.00	646779																				
08-257	268.00	272.00	646780																				
08-257	272.00	273.40	646781																				

Hole 08-258

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FLT
08-258	0.00	5.45																					
08-258	5.45	19.80			0.20	0.00	0.20	0.05	0.00	0.00	ol	W	N	N	N	W	N	N		gy	Du	bksp	sh/50,c/-1
08-258	5.45	8.00	646782																				
08-258	8.00	12.00	646783																				
08-258	12.00	16.00	646784																				
08-258	16.00	20.00	646785																				
08-258	19.80	20.25			0.05	0.00	0.05	0.05	0.00	0.00	ol	M	W	W	N	M	N	N		gy,wt	Flt	sp	sh/-1
08-258	20.00	24.00	646786																				
08-258	20.25	34.00			0.30	0.00	0.30	0.05	0.00	0.00	ol	W	N	N	N	W	N	N		gy	Du	bksp	sh/30,c/-1
08-258	24.00	28.00	646787																				
08-258	28.00	32.00	646788																				
08-258	32.00	36.00	646789																				
08-258	34.00	38.50			0.50	0.00	0.50	0.05	0.00	0.00	ol	W	N	N	N	W	N	N		gy	Du	bksp	sh/50,c/-1
08-258	36.00	40.00	646790	D																			
08-258	38.50	43.80			0.50	0.10	0.60	0.05	0.00	0.00	ol	W	N	N	N	W	N	N		gy	Du	bksp	sh/45,c/-1
08-258	40.00	44.00	646791																				
08-258	43.80	48.00			0.30	0.70	1.00	0.05	0.00	0.00	ol	M	N	N	N	M	N	W	ca	dkgy	spDu	bksp	sh/60,f/20
08-258	44.00	48.00	646792																				
08-258	48.00	57.25			0.50	0.20	0.70	0.05	0.00	0.00	ol	W	N	N	N	W	N	N		gy	Du	bksp	sh/60,c/-1
08-258	48.00	52.00	646793																				
08-258	52.00	56.00	646794																				
08-258	56.00	60.00	646795																				
08-258	57.25	61.80			3.00	0.05	3.00	0.05	0.00	va-0.05	ol	M	N	N	N	W	N	W		dkgy	spDu	bksp	sh/30,c/-1
08-258	60.00	64.00	646796																				
08-258	61.80	65.45			4.00	0.05	4.00	0.05	0.00	0.00	ol	W	N	N	N	W	N	N		gy	Du	bksp	sh/60,c/-1
08-258	64.00	68.00	646797																				
08-258	65.45	69.35			0.20	0.05	0.20	0.05	0.00	0.00	ol	W	N	N	N	W	N	N		gy	Du	bksp	sh/60,c/-1
08-258	68.00	72.00	646798																				
08-258	69.35	89.95			1.00	0.10	1.10	0.10	0.00	0.00	ol	W	N	N	N	W	N	N		gy	Du	bksp	c/-1,sh/55
08-258	72.00	76.00	646799																				
			646800	STD																			
			646801	STD																			
08-258	76.00	80.00	646802																				
08-258	80.00	84.00	646803																				
08-258	84.00	88.00	646804																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-258	88.00	92.00	646805																				
08-258	89.95	91.60			0.20	0.20	0.40	0.00	0.00	va-0.1	cpx	W	N	N	N	M	N	N		ltgy	ocPx,Du	mt	sh/70
08-258	91.60	96.15			0.30	0.10	0.40	0.00	0.00	va-0.05	ol	M	N	N	N	W	N	N		gy	spDu,ocPx	bksp	sh/70,sh/50
08-258	92.00	96.00	646806																				
08-258	96.00	100.00	646807																				
08-258	96.15	105.80			2.00	0.05	2.00	0.05	0.00	va-0.05	cpx	W	N	N	W	W	N	N		ltgy	ocPx	tr	sh/70,c/-1
08-258	100.00	104.00	646808																				
08-258	104.00	105.80	646809																				
08-258	105.80	108.70			0.00	0.05	0.05	0.00	0.00	0.00	hb	N	N	N	N	N	N	N	ca	bnwt	Dk	hb	f/50
08-258	105.80	108.00	646810																				
08-258	108.00	112.00	646811																				
08-258	108.70	110.30			0.20	0.05	0.20	0.05	0.00	py-0.05	ol	M	N	W	W	N	N	N		dkgy	sprDu,Dks	bksp	f/70,f/50
08-258	110.30	111.85			0.00	0.05	0.05	0.00	0.00	va-0.05	tr	W	W	W	W	N	N	N	ma	gngy	altUM	tr,ma	f/70
08-258	111.85	115.70			0.50	0.00	0.50	0.05	0.00	0.00	ol	M	N	N	N	W	N	N		dkgy	spDu	bksp	sh/70,sh/40
08-258	112.00	116.00	646812																				
08-258	115.70	135.25			6.00	1.00	7.00	0.10	0.00	va-0.05	ol	M	N	N	N	W	N	W		dkgy	spDu	bksp	f/30,f/70
08-258	116.00	120.00	646813																				
08-258	120.00	124.00	646814																				
08-258	124.00	128.00	646815																				
08-258	128.00	132.00	646816																				
08-258	132.00	136.00	646817																				
08-258	135.25	141.70			4.00	0.00	4.00	0.20	0.00	0.00	ol	M	N	N	N	M	N	W		dkgy	spDu	bksp	f/70,c/-1
08-258	136.00	140.00	646818																				
08-258	140.00	141.70	646819																				
08-258	141.70	143.55			6.00	0.00	6.00	0.05	0.00	0.00	cpx	W	N	N	N	W	N	N		gy	ocPx	bksp	f/70,c/-1
08-258	141.70	144.00	646820	D																			
08-258	143.55	144.60			1.00	0.00	1.00	0.05	0.00	0.00	cpx	W	N	N	N	W	N	N		gy	ocPx	bksp	f/70
08-258	144.00	148.00	646821																				
08-258	144.60	147.80			1.50	0.05	1.50	0.05	0.00	0.00	ol	W	N	N	N	M	N	N		gy	Du	bksp	c/-1
08-258	147.80	154.40			4.00	1.00	5.00	0.40	0.00	0.00	ol	W	N	N	N	M	N	M		dkgy	grDu	bksp	c/-1,f/70
08-258	148.00	152.00	646822																				
08-258	152.00	154.40	646823																				
08-258	154.40	165.80			0.50	0.05	0.50	0.05	0.00	0.00	ol	W	N	N	N	W	N	N		gy	Wh	bksp	c/-1,sh/45
08-258	154.40	156.00	646824																				
			646825	STD																			

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	temoite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/bf/sh/FLT
			646826	STD																			
08-258	156.00	160.00	646827																				
08-258	160.00	164.00	646828																				
08-258	164.00	168.00	646829																				
			646830	B																			
08-258	165.80	171.90			0.05	0.00	0.05	0.00	0.00	0.00	ol	W	N	N	N	W	N	N		ltgy	WhDu	bksp	c/-1,sh/60
08-258	168.00	172.00	646831																				
08-258	171.90	178.30			0.10	0.10	0.20	0.00	0.00	va-0.05	ol	M	N	W	W	M	N	W		dkgy	Flt	bksp	sh/45,sh/10
08-258	172.00	176.00	646832																				
08-258	176.00	180.00	646833																				
08-258	178.30	182.10			2.50	0.50	3.00	0.10	0.00	0.00	ol	M	N	N	W	M	N	W		dkgy	spDu	bksp,tr	f/45,c/-1
08-258	180.00	184.00	646834																				
08-258	182.10	192.35			0.05	0.10	0.10	0.05	0.00	0.00	ol	W	N	N	W	W	N	N		gy	Du	bksp	sh/45,c/-1
08-258	184.00	188.00	646835																				
08-258	188.00	192.00	646836																				
08-258	192.00	196.00	646837																				
08-258	192.35	197.35			6.90	0.10	7.00	0.30	0.00	va-0.05	ol	M	N	N	W	M	N	W		dkgy	spWh	bksp	c/-1
08-258	196.00	200.00	646838																				
08-258	197.35	201.95			0.80	0.05	0.80	0.10	0.00	0.00	ol	W	N	N	W	M	N	N		gy	Du	mt	f/60,c/-1
08-258	200.00	204.00	646839																				
08-258	201.95	205.05			1.50	0.05	1.50	0.10	0.00	0.00	ol	M	N	N	M	M	N	N		dkgy	sptrWh	bksp,tr	f/45
08-258	204.00	208.00	646840																				
08-258	205.05	216.15			0.05	0.80	0.80	0.05	0.05	0.00	ol	W	N	M	M	M	N	N	bt,ca	gngy	trspWh,ocPx	tr	f/60,f/35
08-258	208.00	212.00	646841																				
08-258	212.00	216.00	646842																				
08-258	216.00	220.00	646843																				
08-258	216.15	220.80			0.05	0.00	0.05	0.00	0.00	0.00	ol	M	N	N	M	M	N	N		dkgy	trspDu	tr,bksp	f/70,f/30
08-258	220.00	224.00	646844																				
08-258	220.80	227.60			0.50	0.00	0.50	0.05	0.00	0.00	ol	W	N	N	M	M	N	N	bt	gy	trWh	tr	c/-1,f/70
08-258	224.00	228.00	646845																				
08-258	227.60	229.65			0.05	0.05	0.05	0.00	0.00	0.00	ol	M	N	W	M	M	N	N	bt	gy	Flt	tr	sh/70,sh/-1
08-258	228.00	232.00	646846																				
08-258	229.65	253.90			1.50	0.00	1.50	0.08	0.00	0.00	ol	W	N	N	M	M	N	N		gy	trDu	tr	c/-1,f/35
08-258	232.00	236.00	646847																				
08-258	236.00	240.00	646848																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FLT
08-258	240.00	244.00	646849																				
			646850	STD																			
			646851	STD																			
08-258	244.00	248.00	646852																				
08-258	248.00	252.00	646853																				
08-258	252.00	256.00	646854																				
08-258	253.90	256.40			0.70	0.00	0.70	0.05	0.00	0.00	cpx	W	N	N	M	W	N	N		gywt	trocPx	tr	c/-1,f/60
08-258	256.00	260.00	646855																				
08-258	256.40	258.65			2.90	0.10	3.00	0.10	0.05	0.00	ol	M	N	N	M	M	N	N		dkgy	trspWh	tr,bksp	f/70,c/-1
08-258	258.65	264.10			1.00	2.00	3.00	0.10	0.20	0.00	cpx	W	N	N	I	W	N	N		gy	trocPx	tr,bksp	c/-1,f/45
08-258	260.00	264.00	646856																				
08-258	264.00	268.00	646857																				
08-258	264.10	269.20			2.00	0.00	2.00	0.05	0.00	0.00	ol	M	N	M	I	N	N	N		gn,dkgy	trspWh	tr,bksp	sh/10,sh/50
08-258	268.00	272.00	646858																				
08-258	269.20	275.85			0.70	1.50	2.20	0.05	0.00	0.00	cpx	M	N	W	I	N	N	N	ma	gn,dkgy	trocPxWh	tr,bksp	sh/50,c/-1
08-258	272.00	275.85	646859																				

Hole 08-259

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
			646860	B																			
08-259	0.00	3.00																					
08-259	3.00	11.75			0.50	0.00	0.50	0.25	0.00	0.00	ol	M	W	N	W	W	N	N		dkgy,gn	spgDu	bksp	c/-1,f/70
08-259	3.00	4.00	646861																				
08-259	4.00	8.00	646862																				
08-259	8.00	12.00	646863																				
08-259	11.75	21.65			0.05	0.00	0.05	0.05	0.00	0.00	ol	W	W	N	N	W	N	N	bt	gn	gDu	bksp	c/-1,f/70
08-259	12.00	16.00	646864																				
08-259	16.00	20.00	646865																				
08-259	20.00	24.00	646866																				
08-259	21.65	29.45			1.40	0.10	1.50	0.05	0.00	va-0.05	ol	M	W	W	W	M	N	N	bt	dkgy	spDu	bksp	f/35,f/65
08-259	24.00	28.00	646867																				
08-259	28.00	32.00	646868																				
08-259	29.45	38.55			0.30	0.05	0.30	0.05	0.00	0.00	ol	W	N	N	M	W	N	N	bt	gy	trWh	tr	c/-1,f/60
08-259	32.00	36.00	646869																				
08-259	36.00	38.55	646870																				
08-259	38.55	44.80			4.90	0.10	5.00	0.05	0.00	va-0.05	ol	W	N	N	M	M	N	N		gy	trWh	tr,bksp	f/40,f/60
08-259	38.55	40.00	646871																				
08-259	40.00	44.00	646872																				
08-259	44.00	48.00	646873																				
08-259	44.80	47.20			0.30	0.10	0.40	0.05	0.00	0.00	ol	M	W	N	M	W	N	N	ca	dkgy	trspWh	tr,bksp	f/45
08-259	47.20	67.65			1.00	0.00	1.00	0.10	0.00	0.00	ol	W	N	N	M	M	N	N		gngy	trWh	tr,bksp	f/45,sh/20
08-259	48.00	52.00	646874																				
			646875	STD																			
			646876	STD																			
08-259	52.00	56.00	646877																				
08-259	56.00	60.00	646878																				
08-259	60.00	64.00	646879																				
08-259	64.00	68.00	646880	D																			
08-259	67.65	75.50			0.80	0.05	0.80	0.30	0.00	0.00	ol	M	N	N	M	M	N	N		dkgy	sptrDu	bksp,tr	sh/70,sh/30
08-259	68.00	72.00	646881																				
08-259	72.00	76.00	646882																				
08-259	75.50	79.40			1.00	0.10	1.00	0.05	0.00	0.00	ol	M	M	W	M	M	N	N	cb	gn,dkgy	sptrDu	sp,tr	sh/70,sh/30
08-259	76.00	80.00	646883																				
08-259	79.40	84.30			3.40	0.10	3.50	0.05	0.00	0.00	ol	M	N	N	M	M	N	N	cb	gn,dkgy	trspWh	tr,bksp	f/70,f/30

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	temoite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-259	80.00	84.00	646884																				
08-259	84.00	88.00	646885																				
08-259	84.30	87.00			0.05	0.50	0.50	0.00	0.00	va-0.2	ol	W	N	W	I	W	N	N	cb	gn,dkgy	trWh	tr,cb	f/15,f/45
08-259	87.00	89.05			0.00	0.20	0.20	0.00	0.00	0.00	sp	I	N	N	M	W	N	N	cb	bk	sptrWh	bksp,tr	sh/40,sh/0
08-259	88.00	90.15	646886																				
08-259	89.05	90.15			0.05	0.05	0.05	0.05	0.00	0.00	ol	M	N	W	I	N	N	N	cb	dkgy	trspWh,ocPx	tr,bksp	sh/10,sh/40
08-259	90.15	101.00			0.00	2.00	2.00	0.00	0.00	py-0.05	qtz	N	N	W	N	N	N	M	cb,bt	gygnbn	Hfs	qtz	f/60
08-259	90.15	92.00	646887																				
08-259	92.00	96.00	646888																				
08-259	96.00	100.00	646889																				
			646890	B																			
08-259	100.00	104.00	646891																				
08-259	101.00	106.55			0.00	2.00	2.00	0.00	0.00	0.00	cpx	W	N	N	W	N	N	N	cb	ltgy	altcPx	tr	f/60
08-259	104.00	108.00	646892																				
08-259	106.55	109.75			0.00	0.20	0.20	0.00	0.00	0.00	chl	N	N	N	N	N	N	N	cb	dkbngn	HfsDk	chl	c/-1
08-259	108.00	112.00	646893																				
08-259	109.75	114.00			0.00	0.50	0.50	0.00	0.00	0.00	qtz	N	N	N	N	N	N	W		gygn	Hfs	qtz	f/70
08-259	112.00	116.00	646894																				
08-259	114.00	116.00			0.00	4.00	4.00	0.00	0.00	0.00	chl	N	N	N	N	N	N	N		or,gn	Hfs,Dk	chl	f/75
08-259	116.00	117.95			0.00	2.00	2.00	0.00	0.00	0.00	cb	W	N	N	W	N	N	N	cb	wtgy	cbUM	ma	f/70
08-259	116.00	120.00	646895																				
08-259	117.95	121.25			0.00	0.10	0.10	0.00	0.00	0.00	cpx	W	N	N	M	N	N	N	cb	bngy	altocPx	tr	f/35,f/70
08-259	120.00	124.00	646896																				
08-259	121.25	132.30			0.00	1.00	1.00	0.00	0.00	py-0.05	qtz	N	N	N	N	N	N	W	cb	gnbngy	Hfs	qtz	f/40
08-259	124.00	128.00	646897																				
08-259	128.00	132.00	646898																				
08-259	132.00	136.00	646899																				
			646900	STD																			
			646901	STD																			
08-259	132.30	136.10			0.00	1.00	1.00	0.00	0.00	0.00	cpx	W	W	N	I	W	N	N	cb	gngy	trocPx	tr	f/35,f/70
08-259	136.00	140.00	646902																				
08-259	136.10	163.35			3.00	0.50	3.50	0.30	0.00	0.00	sp	I	N	N	M	M	N	N		bk	sptrDu	bksp,tr	c/-1,f/40
08-259	140.00	144.00	646903																				
08-259	144.00	148.00	646904																				
08-259	148.00	152.00	646905																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-259	152.00	156.00	646906																				
08-259	156.00	160.00	646907																				
08-259	160.00	164.00	646908																				
08-259	163.35	178.95			3.00	0.05	3.00	0.20	0.00	0.00	ol	M	N	N	M	M	N	N		dkgy	trspDu	tr,bksp	sh/60,c/-1
08-259	164.00	168.00	646909																				
08-259	168.00	172.00	646910	D																			
08-259	172.00	176.00	646911																				
08-259	176.00	180.00	646912																				
08-259	178.95	185.60			5.00	0.00	5.00	1.50	0.00	0.00	ol	I	N	N	M	M	N	N		dkgy-bk	sptrDu	bksp,tr	c/-1,sh/60
08-259	180.00	184.00	646913																				
08-259	184.00	188.00	646914																				
08-259	185.60	187.20			0.00	0.50	0.50	0.00	0.00	va-0.1	sp	I	W	N	M	M	N	N	ep,chl	bk,gnbn	spaltDk	bksp,ep	sh/70
08-259	187.20	201.55			2.50	0.05	0.50	0.30	0.00	va-0.05	ol	I	W	N	M	I	N	W		bk	sptrDu	bksp,tr	c/-1,sh/70
08-259	188.00	192.00	646915																				
08-259	192.00	196.00	646916																				
08-259	196.00	200.00	646917																				
08-259	200.00	204.00	646918																				
08-259	201.55	223.95			2.90	0.10	3.00	0.10	0.00	va-0.1	ol	M	N	N	M	I	N	N		dkgy	trspDu	tr,bksp	c/-1,f/70
08-259	204.00	208.00	646919																				
			646920	B																			
08-259	208.00	212.00	646921																				
08-259	212.00	216.00	646922																				
08-259	216.00	220.00	646923																				
08-259	220.00	224.00	646924																				
			646925	STD																			
			646926	STD																			
08-259	223.95	225.45			5.00	2.00	7.00	0.50	0.10	0.00	ol	I	M	N	M	I	N	W		bk	sptrDu,altDk	bksp,tr	sh/30,sh/-1
08-259	224.00	228.00	646927																				
08-259	225.45	239.85			3.70	0.30	4.00	0.20	0.00	0.00	ol	M	N	N	M	I	N	N		dkgy	trspDu	tr,bksp	c/-1,f/65
08-259	228.00	232.00	646928																				
08-259	232.00	236.00	646929																				
08-259	236.00	240.00	646930																				
08-259	239.85	242.85			0.80	0.00	0.80	0.05	0.00	0.00	ol	M	N	N	M	M	N	N		dkgy	trspWh,altDk	tr,bksp	f/45
08-259	240.00	244.00	646931																				
08-259	242.85	252.10			2.00	1.00	3.00	0.05	0.05	0.00	cpX	M	W	N	M	M	N	N		dkgy	trrocPx	tr,bksp	f/45

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-259	244.00	248.00	646932																				
08-259	248.00	252.00	646933																				
08-259	252.00	256.00	646934																				
08-259	252.10	258.15			2.00	0.00	2.00	0.20	0.00	0.00	ol	M	N	N	M	I	N	N	ca	dkgy	trspWh	tr,bksp	f/45,f/30
08-259	256.00	260.00	646935																				
08-259	258.15	260.35			0.00	0.50	0.50	0.00	0.00	0.00	hb	N	N	N	N	N	N	N		dkbngn	altDk	chl,hb	f/45
08-259	260.00	264.00	646936																				
08-259	260.35	265.40			0.20	0.05	0.20	0.05	0.00	0.00	cpx	M	N	N	I	N	N	N		gy	trocPx	tr,bksp	f/45,c/-1
08-259	264.00	268.00	646937																				
08-259	265.40	269.15			0.20	0.30	0.50	0.00	0.10	va-0.05	cpx	W	N	N	I	N	N	N		gy	trocPx	tr	c/-1,f/30
08-259	268.00	272.00	646938																				
08-259	269.15	275.95			1.00	0.05	1.00	0.10	0.05	0.00	cpx	M	N	N	M	M	N	W	ca	gy	trocPx,trspDu	tr,bksp	f/30,f/45
08-259	272.00	276.00	646939																				
08-259	275.95	287.25			0.30	0.00	0.30	0.05	0.00	0.00	ol	W	N	N	M	I	N	N		gy	trspWh	tr,bksp	f/30,c/-1
08-259	276.00	280.00	646940	D																			
08-259	280.00	284.00	646941																				
08-259	284.00	288.00	646942																				
08-259	287.25	290.45			1.00	10.00	11.00	0.10	1.00	0.00	cpx	M	N	N	M	M	N	W		gy	trocPx	tr,bsp	sh/70
08-259	288.00	290.45	646943																				
08-259	290.45	292.10			1.50	0.00	1.50	0.30	0.00	0.00	hb	M	N	N	M	M	N	N		gybn	altDk,sptrDu	tr	f/70,f/30
08-259	290.45	292.00	646944																				
08-259	292.00	296.00	646945																				
08-259	292.10	300.85			3.00	0.05	3.00	0.30	0.00	va-0.05	ol	M	N	N	W	M	N	N		dkgy	spDu	bksp,tr	f/30,f/70
08-259	296.00	300.85	646946																				

Hole 08-260

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/bf/sh/FLT
08-260	0.00	4.35																					
08-260	4.35	15.90			0.10	0.05	0.15	0.05	0.00	0.00	ol	W	W	N	W	W	N	W	ca	gy	Du	sp	f/40
08-260	4.35	8.00	646947																				
08-260	8.00	12.00	646948																				
08-260	12.00	16.00	646949																				
			646950	STD																			
			646951	STD																			
08-260	15.90	16.75			1.00	0.30	1.30	0.10	0.00	0.00	ol	W	W	N	W	W	N	N	ca	mdgy	spDu	sp	c/-1
08-260	16.00	20.00	646952																				
08-260	16.75	44.35			0.20	0.20	0.40	0.10	0.00	0.00	ol,cpx	W	W	N	M	W	N	N	ca,bt	bk,gy	trWh	tr	b/-1,f/75
08-260	20.00	24.00	646953																				
08-260	24.00	28.00	646954																				
08-260	28.00	32.00	646955																				
08-260	32.00	36.00	646956																				
08-260	36.00	40.00	646957																				
08-260	40.00	44.00	646958																				
08-260	44.00	48.00	646959																				
08-260	44.35	51.20			7.00	5.00	12.00	2.00	0.50	0.00	ol	W	W	N	M	W	N	M	ca,bt	mdbk,gy	trWh,GS	tr	sh/80
08-260	48.00	52.00	646960																				
08-260	51.20	52.65			15.00	5.00	20.00	3.00	0.05	0.00	ol	M	W	N	M	W	N	M		mdgy,bk	trDu,MS	tr	c/-1
08-260	52.00	56.00	646961																				
08-260	52.65	54.60			5.00	3.00	8.00	1.00	0.10	0.00	ol	W	W	N	M	W	N	W	ca	bkggy	trWh	tr	f/55
08-260	54.60	55.65			0.00	5.00	5.00	0.00	1.00	0.00	si	W	N	N	N	N	N	M		mdgy	MSD	alt	f/60
08-260	55.65	57.45			0.30	0.20	0.50	0.10	0.10	0.00	ol	W	W	N	M	W	N	M	ca	mdgybk	trWh	tr	f/50
08-260	56.00	60.00	646962																				
08-260	57.45	60.60			3.00	1.00	4.00	0.80	0.10	0.00	ol	W	W	N	M	W	N	M	ca	mdgybk	trWh	tr	f/60
08-260	60.00	64.00	646963																				
08-260	60.60	61.50			6.00	2.00	8.00	1.00	0.10	0.00	ol	W	W	N	M	W	N	M	ca	mdgybk	trWh	tr	c/-1
08-260	61.50	62.60			0.20	0.10	0.30	0.05	0.05	0.00	ol	W	W	N	M	W	N	M	ca	mdgybk	trWh	tr	b/-1
08-260	62.60	63.25			8.00	2.00	10.00	1.00	0.10	0.00	ol	W	W	N	M	W	N	M	ca	mdgybk	trWh	tr	c/-1
08-260	63.25	67.15			0.50	0.10	0.60	0.05	0.05	0.00	ol	W	W	N	I	W	N	M	ca	mdgybk	trWh	tr	f/60,bx
08-260	64.00	68.00	646964																				
08-260	67.15	74.10			3.00	0.50	3.50	1.00	0.00	0.00	ol	W	W	N	I	W	N	M	ca	mdgybk	trWh	tr	f/45,sh/80
08-260	68.00	72.00	646965																				
08-260	72.00	76.00	646966																				

SAMPLE DATA					SULPHIDES						SIL	MINERALOGY								GEOLOGY			
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-260	74.10	75.60			5.00	3.00	8.00	2.00	0.10	0.00	ol	W	W	N	I	W	N	M	ca	mdgybk	trWh	tr	c/-1
08-260	75.60	77.50			2.00	1.00	3.00	0.20	0.00	0.00	ol	W	W	N	I	W	N	M	ca	mdgybk	trWh	tr	b/-1
08-260	76.00	80.00	646967																				
08-260	77.50	91.20			0.20	0.05	0.25	0.05	0.00	0.00	ol	W	W	N	M	W	N	W	ca,bt	gy	trDu	tr	f/80
08-260	80.00	84.00	646968																				
08-260	84.00	88.00	646969																				
08-260	88.00	92.00	646970	D																			
08-260	91.20	99.60			4.00	0.50	4.50	1.50	0.05	py-0.05	ol	M	W	N	M	W	N	W	ca,bt	gy	trDu	tr	f/40
08-260	92.00	96.00	646971																				
08-260	96.00	100.00	646972																				
08-260	99.60	105.60			0.20	0.05	0.25	0.05	0.00	0.00	ol	W	W	N	M	W	N	W	ca,bt	gy	trDu	tr	f/50
08-260	100.00	104.00	646973																				
08-260	104.00	108.00	646974																				
			646975	STD																			
			646976	STD																			
08-260	105.60	109.25			2.00	3.00	5.00	1.00	0.30	0.00	ol	M	W	N	M	W	N	W	ca,ep	mdgy	trWh	tr	f/45
08-260	108.00	112.00	646977																				
08-260	109.25	115.75			1.00	0.50	1.50	0.30	0.10	0.00	ol	M	W	N	M	W	N	W	ca,ep	mdgy	trWh	tr	f/50
08-260	112.00	116.00	646978																				
08-260	115.75	118.30			10.00	5.00	15.00	2.00	0.10	0.00	cpx	W	W	N	W	M	N	M	ca	ltgy	ocPx,MGS	gr	c/-1,f/70
08-260	116.00	120.00	646979																				
			646980	B																			
08-260	118.30	124.50			5.00	1.00	7.00	1.00	0.05	0.00	ol	M	W	N	W	W	N	W	ca	mdgy	trWh	tr	c/-1,f/80
08-260	120.00	124.00	646981																				
08-260	124.00	128.00	646982																				
08-260	124.50	153.60			0.80	0.20	1.00	0.40	0.20	0.00	ol	W	W	N	W	W	N	W	ca	gy	trDu	tr	f/40
08-260	128.00	132.00	646983																				
08-260	132.00	136.00	646984																				
08-260	136.00	140.00	646985																				
08-260	140.00	144.00	646986																				
08-260	144.00	148.00	646987																				
08-260	148.00	152.00	646988																				
08-260	152.00	156.00	646989																				
08-260	153.60	158.55			1.00	0.20	1.20	0.50	0.20	0.00	ol	W	W	N	M	W	N	M	ca	gy	trDu	tr	f/60
08-260	156.00	160.00	646990																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FLT
08-260	158.55	164.10			8.00	4.00	12.00	2.50	0.50	0.00	ol	M	W	N	M	W	N	M	ca	mdgy	trspDuWh,MGS	tr	c/-1,f/85
08-260	160.00	164.00	646991																				
08-260	164.00	168.00	646992																				
08-260	164.10	173.60			8.00	4.00	12.00	4.00	1.00	0.00	ol	M	W	N	M	W	N	M		mdgy	trspWh	tr	c/-1,f/85
08-260	168.00	172.00	646993																				
08-260	172.00	176.00	646994																				
08-260	173.60	179.15			0.80	0.20	1.00	0.10	0.05	0.00	ol	W	M	W	W	W	N	W	ca	mdgy,gn	sptrDu	sp	ft/30
08-260	176.00	180.00	646995																				
08-260	179.15	184.10			0.30	0.10	0.40	0.05	0.00	va?	ol	M	W	W	N	M	N	W	ca	dkgy	spDu	sp	sh/60
08-260	180.00	184.00	646996																				
08-260	184.00	188.00	646997																				
08-260	184.10	190.65			0.40	0.10	0.50	0.10	0.00	va?	ol,si	M	W	W	W	M	N	W	ca	dkgy,pkwt	sptrWh,CSDk	sp	f/70
08-260	188.00	192.00	646998																				
08-260	190.65	202.55			0.90	0.10	1.00	0.30	0.00	va?	ol	M	W	N	W	M	N	W	ca	dkgy	spDu	sp	c/-1,f/60
08-260	192.00	196.00	646999																				
			647000	STD																			
			647001	STD																			
08-260	196.00	200.00	647002																				
08-260	200.00	204.00	647003																				
08-260	202.55	217.00			0.05	0.05	0.05	0.05	0.00	0.00	ol	W	W	N	N	W	N	N	ca	gy	Du	sp	c/-1,f/60
08-260	204.00	208.00	647004																				
08-260	208.00	212.00	647005																				
08-260	212.00	216.00	647006																				
08-260	216.00	220.00	647007																				
08-260	217.00	219.70			0.00	0.00	0.00	0.00	0.00	0.00	si	N	W	W	N	N	N	N	ca	bngy	btfsDk	bt	c/-1,sh/85
08-260	219.70	230.95			0.10	0.05	0.15	0.05	0.00	0.00	ol	W	W	N	N	W	N	W	ca	gy	Du	sp	c/-1,f/55
08-260	220.00	224.00	647008																				
08-260	224.00	228.00	647009																				
			647010	B																			
08-260	228.00	232.00	647011																				
08-260	230.95	242.65			0.20	0.10	0.30	0.10	0.00	0.00	ol	M	W	N	N	W	N	W	ca	mdgy	spDu	sp	sh/60,f/50
08-260	232.00	236.00	647012																				
08-260	236.00	240.00	647013																				
08-260	240.00	244.00	647014																				
08-260	242.65	253.90			0.10	0.05	0.15	0.05	0.00	0.00	ol	M	W	N	W	W	N	W	ca	mdgy	sptrDu	sp	f/60

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY								GEOLOGY				
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FLT
08-260	244.00	248.00	647015																				
08-260	248.00	252.00	647016																				
08-260	252.00	256.00	647017																				
08-260	253.90	259.70			0.00	0.00	0.00	0.00	0.00	0.00	ol	W	M	W	W	W	N	N	ca	ltgy	altFlt	alt	ft/-1,sh/60
08-260	256.00	260.00	647018																				
08-260	259.70	262.00			0.10	0.00	0.10	0.05	0.00	0.00	ol	M	W	W	N	W	N	W		md-dkgy	spDu	sp	sh/50
08-260	260.00	264.00	647019																				
08-260	262.00	269.40			1.00	0.10	1.10	0.10	0.00	0.00	ol	M	W	N	W	W	N	M		mdgy	spDu	sp	f/80
08-260	264.00	268.00	647020																				
08-260	268.00	272.00	647021																				
08-260	269.40	292.40			0.80	0.20	1.00	0.20	0.00	0.00	ol	M	W	N	W	M	N	W		mdgy	spDu	sp	f/85
08-260	272.00	276.00	647022																				
08-260	276.00	280.00	647023																				
08-260	280.00	284.00	647024																				
			647025	STD																			
			647026	STD																			
08-260	284.00	288.00	647027																				
08-260	288.00	292.00	647028																				
08-260	292.00	296.00	647029																				
08-260	292.40	300.25			0.20	0.10	0.30	0.05	0.00	0.00	ol	M	W	N	W	M	N	W	gt,chy	mdgy	spDu	sp	f/50,sh/-1
08-260	296.00	300.00	647030	D																			
08-260	300.00	304.00	647031																				
08-260	300.25	307.80			0.80	0.20	1.00	0.20	0.00	0.00	ol	M	W	N	W	M	N	W	gt,chy	mdgy	spDu	sp	c/-1,f/50
08-260	304.00	308.00	647032																				
08-260	307.80	325.90			0.60	0.40	1.00	0.30	0.00	0.00	ol	M	W	N	N	M	N	W	gt,chy	mdgy	spDu	sp	f/65
08-260	308.00	312.00	647033																				
08-260	312.00	316.00	647034																				
08-260	316.00	320.00	647035																				
08-260	320.00	324.00	647036																				
08-260	324.00	328.00	647037																				
08-260	325.90	333.75			3.50	0.50	4.00	1.00	0.00	0.00	ol	M	W	N	N	M	N	W	gt,chy	mdgy	spDu	sp	c/-1,f/45
08-260	328.00	331.00	647038																				
08-260	331.00	333.75	647039																				
			647040	B																			

Hole 08-261

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-261	0.00	5.35																					
08-261	5.35	9.80			0.00	0.05	0.05	0.05	0.00	0.00	ol	M	N	N	N	W	N	N		dkgy	spgDu	bksp	sh/70,c/-1
08-261	5.35	8.00	647041																				
08-261	8.00	12.00	647042																				
08-261	9.80	21.15			0.00	0.05	0.05	0.05	0.00	0.00	ol	W	N	N	N	W	N	N		gngy	gDu	bksp	c/-1,f/45
08-261	12.00	16.00	647043																				
08-261	16.00	20.00	647044																				
08-261	20.00	24.00	647045																				
08-261	21.15	28.90			0.00	0.10	0.10	0.05	0.00	0.00	ol	M	N	N	N	W	N	N		gy	spgDu	bksp	c/-1,sh/45
08-261	24.00	28.00	647046																				
08-261	28.00	32.00	647047																				
08-261	28.90	30.45			0.00	0.05	0.05	0.05	0.00	0.00	ol	W	W	W	N	W	N	N		bngy	spDu,altDk	bksp	sh/45
08-261	30.45	36.35			0.00	0.10	0.10	0.05	0.00	0.00	ol	M	N	N	N	W	N	N		dkgy	spgDu	bksp	sh/40
08-261	32.00	36.00	647048																				
08-261	36.00	40.00	647049																				
			647050	STD																			
			647051	STD																			
08-261	36.35	41.15			0.00	0.05	0.05	0.05	0.00	0.00	ol	W	N	N	N	W	N	N		gngy	gDu	bksp	c/-1,sh/50
08-261	40.00	44.00	647052																				
08-261	41.15	49.00			0.00	0.05	0.05	0.05	0.00	0.00	ol	M	W	N	N	W	N	N	cb	gngy	spgDu	sp	sh/45,sh/60
08-261	44.00	48.00	647053																				
08-261	48.00	52.00	647054																				
08-261	49.00	65.80			0.00	0.05	0.05	0.05	0.00	0.00	ol	W	N	N	N	W	N	N		gngy	gDu	bksp	c/-1,sh/45
08-261	52.00	56.00	647055																				
08-261	56.00	60.00	647056																				
08-261	60.00	64.00	647057																				
08-261	64.00	68.00	647058																				
08-261	65.80	69.20			0.00	0.10	0.10	0.05	0.00	0.00	ol	M	N	N	W	W	N	N		dkgy	spgDu	bksp	c/-1,sh/30
08-261	68.00	72.00	647059																				
08-261	69.20	73.10			0.00	0.05	0.05	0.05	0.00	0.00	ol	M	W	W	W	M	N	N	cb	dkgy	spDu	bksp	sh/30,sh/0
08-261	72.00	76.00	647060	D																			
08-261	73.10	78.20			0.00	0.05	0.05	0.05	0.00	0.00	ol	W	W	N	M	W	N	N	N	gy	trDu	tr	c/-1,sh/70
08-261	76.00	80.00	647061																				
08-261	78.20	81.15			0.00	0.05	0.05	0.05	0.00	0.00	bksp	I	W	W	W	M	N	N	cb	bk	sp	bksp	sh/30,sh/0
08-261	80.00	84.00	647062																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FLT
08-261	81.15	85.15			0.00	0.20	0.20	0.20	0.00	0.00	ol	M	W	N	M	M	N	N	cb	dkgy	sptrDu	bksp	sh/30,sh/65
08-261	84.00	88.00	647063																				
08-261	85.15	86.80			0.00	0.10	0.10	0.10	0.00	0.00	bksp	I	W	N	W	M	N	N	cb	bk	Sp	bksp	sh/30,sh/0
08-261	86.80	94.70			0.00	0.05	0.05	0.05	0.00	0.00	sp	I	N	N	N	I	N	N		bk	Flt	bksp	sh/-1
08-261	88.00	92.00	647064																				
08-261	92.00	96.00	647065																				
08-261	94.70	97.95			0.00	0.10	0.10	0.05	0.00	0.00	sp	M	W	N	N	W	N	W	cb,qtz	ltgn	Flt	qtz	sh/50,sh/-1
08-261	96.00	100.00	647066																				
08-261	97.95	100.00			0.00	0.10	0.10	0.00	0.00	va-0.05	gr	M	W	N	N	N	N	I		bk	Flt	gr	sh/40,sh/-1
08-261	100.00	101.60			0.00	0.10	0.10	0.00	0.00	va-0.1	sp	M	M	N	W	N	N	W	cb	dkgygn	Sp	sp	sh/45
08-261	100.00	104.00	647067																				
08-261	101.60	105.55			0.05	0.20	0.20	0.20	0.00	0.00	ol	M	N	N	M	M	N	N		dkgy	sptrDu	bksp,tr	sh/60
08-261	104.00	108.00	647068																				
08-261	105.55	136.85			0.00	0.05	0.25	0.05	0.00	0.00	ol	W	W	W	M	M	N	N	cb	ltgy	trDu	tr	c/-1,sh/65
08-261	108.00	112.00	647069																				
			647070	B																			
08-261	112.00	116.00	647071																				
08-261	116.00	120.00	647072																				
08-261	120.00	124.00	647073																				
08-261	124.00	128.00	647074																				
			647075	STD																			
			647076	STD																			
08-261	128.00	132.00	647077																				
08-261	132.00	136.00	647078																				
08-261	136.00	140.00	647079																				
08-261	136.85	142.70			0.00	0.05	0.05	0.05	0.00	0.00	ol	M	W	W	M	M	N	N	cb	dkgy	trspDu	tr,bksp	sh/65,sh/40
08-261	140.00	144.00	647080																				
08-261	142.70	144.90			0.00	0.05	0.05	0.05	0.00	0.00	ol	M	N	W	W	W	N	W	cb	bngy	Flt	bksp	sh/45,f/-1
08-261	144.00	148.00	647081																				
08-261	144.90	155.95			1.30	0.20	1.50	0.20	0.00	0.00	ol	M	N	N	M	M	N	W		dkgy	sptrDu	bksp,tr	sh/45,sh/30
08-261	148.00	152.00	647082																				
08-261	152.00	156.00	647083																				
08-261	155.95	160.80			1.50	0.05	1.50	0.05	0.00	0.00	hb	W	W	W	W	W	N	N	ep	dkbn	altDk,sptrDu	ep,sp	sh/60
08-261	156.00	160.00	647084																				
08-261	160.00	164.00	647085																				

SAMPLE DATA					SULPHIDES						SIL	MINERALOGY							GEOLOGY				
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/bf/sh/FLT
08-261	160.80	185.00			1.50	0.50	2.00	0.10	0.00	va-0.05	bksp	I	W	N	M	M	N	W		bk	sptrDu	bksp,tr	sh/60,sh/30
08-261	164.00	168.00	647086																				
08-261	168.00	172.00	647087																				
08-261	172.00	176.00	647088																				
08-261	176.00	180.00	647089																				
08-261	180.00	184.00	647090	D																			
08-261	184.00	188.00	647091																				
08-261	185.00	189.55			3.00	0.05	3.00	0.30	0.00	0.00	ol	M	N	N	M	W	N	N		dkgy	trspDu	tr,bksp	c/-1,sh/60
08-261	188.00	192.00	647092																				
08-261	189.55	193.50			2.00	0.00	2.00	0.20	0.00	0.00	ol	M	N	N	M	W	N	N		dkgy	trspDu	tr,bksp	c/-1,sh/60
08-261	192.00	196.00	647093																				
08-261	193.50	211.60			0.20	0.00	0.20	0.05	0.00	0.00	ol	M	W	N	M	W	N	N		dkgy	trspDu	tr,bksp	c/-1,sh/45
08-261	196.00	200.00	647094																				
08-261	200.00	204.00	647095																				
08-261	204.00	208.00	647096																				
08-261	208.00	212.00	647097																				
08-261	211.60	217.60			0.80	0.20	1.00	0.10	0.00	0.00	ol	M	N	N	M	W	N	W		dkgy	trspDu	tr,bksp	sh/60,sh/20
08-261	212.00	216.00	647098																				
08-261	216.00	220.00	647099																				
			647100	STD																			
			647101	STD																			
08-261	217.60	241.75			4.00	0.05	4.00	0.10	0.00	va-0.05	ol	M	N	N	M	W	N	M		dkgy	trspDu	tr,bksp	sh/45,sh/60
08-261	220.00	224.00	647102																				
08-261	224.00	228.00	647103																				
08-261	228.00	232.00	647104																				
08-261	232.00	236.00	647105																				
08-261	236.00	240.00	647106																				
08-261	240.00	244.00	647107																				
08-261	241.75	249.30			1.00	0.05	1.00	0.05	0.00	0.00	ol	M	N	N	M	W	N	W		dkgy	trspDu	tr,bksp	sh/45,sh/70
08-261	244.00	248.00	647108																				
08-261	248.00	252.00	647109																				
08-261	249.30	251.40			0.50	0.00	0.50	0.05	0.00	0.00	ol	W	N	N	M	W	N	N		gy	trDu	tr,bksp	sh/30
08-261	251.40	256.15			4.00	0.05	4.00	0.20	0.00	va-0.05	ol	M	N	N	M	M	N	W		dkgy	sptrDu	bksp,tr	sh/30,c/-1
08-261	252.00	256.00	647110																				
08-261	256.00	260.00	647111																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FLT
08-261	256.15	258.50			0.05	0.10	0.10	0.05	0.00	va-0.05	sp	I	N	N	M	M	N	W		bk	Sp	bksp	sh/65,sh/20
08-261	258.50	270.00			1.00	0.05	1.00	0.05	0.00	0.00	ol	M	N	N	M	W	N	M		dkgy	trspDu	tr,bksp	c/-1,sh/45
08-261	260.00	264.00	647112																				
08-261	264.00	268.00	647113																				
08-261	268.00	272.00	647114																				
08-261	270.00	271.65			0.20	0.05	0.20	0.05	0.00	0.00	ol	I	W	N	M	M	N	W		bk	sptrDu	bksp,tr	sh/50
08-261	271.65	276.10			0.50	0.00	0.50	0.05	0.00	0.00	ol	M	N	N	M	M	N	N	cb	gy	trspDu	tr,bksp	sh/45,sh/30
08-261	276.00	280.00	647116																				
08-261	276.10	287.30			0.05	0.05	0.05	0.05	0.00	0.00	ol	M	N	N	M	W	N	N	cb	dkgy	trspDu	tr,bksp	sh/60,c/-1
08-261	280.00	284.00	647117																				
08-261	284.00	288.00	647118																				
08-261	287.30	291.65			0.00	0.05	0.05	0.00	0.05	va-0.05	sp	M	M	N	M	N	N	W	cb	dkgy	Flt	sp,cb	sh/-1
08-261	288.00	292.00	647119																				
08-261	291.65	293.10			2.00	38.00	40.00	1.00	1.00	0.00	po	W	N	N	W	W	N	I		bngy	GS,ocPx	gr	f/55
08-261	292.00	293.10	647120	D																			
08-261	293.10	304.35			0.50	0.50	1.00	0.05	0.05	0.00	ol	W	N	W	M	M	N	W		gy	trocPx,trspDu	tr,bksp	c/-1,f/60
08-261	293.10	296.00	647121																				
08-261	296.00	300.00	647122																				
08-261	300.00	304.00	647123																				
08-261	304.00	308.00	647124																				
			647125	STD																			
			647126	STD																			
08-261	304.35	318.45			0.00	5.00	5.00	0.00	0.25	0.00	cpx	W	N	W	M	N	N	M	cb	gngy	trocPx	tr	sh/30,c/-1
08-261	308.00	312.00	647127																				
08-261	312.00	316.00	647128																				
08-261	316.00	318.45	647129																				
			647130	B																			
08-261	318.45	325.85			3.00	0.50	3.50	0.40	0.05	va-0.05	ol	W	W	N	M	W	N	N		gy	trWh	tr,bksp	c/-1,sh/40
08-261	318.45	320.00	647131																				
08-261	320.00	324.00	647132																				
08-261	324.00	328.00	647133																				
08-261	325.85	345.85			5.00	0.50	5.50	1.00	0.05	va-0.1	ol	W	W	N	M	W	N	W		gy	trDu	tr,bksp	c/-1,sh/35
08-261	328.00	332.00	647134																				
08-261	332.00	336.00	647135																				
08-261	336.00	340.00	647136																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FLT
08-261	340.00	344.00	647137																				
08-261	344.00	348.00	647138																				
08-261	345.85	353.15			2.00	0.10	2.10	0.40	0.00	va-0.05	ol	M	W	N	M	M	N	N		gy	trspDu	tr,bksp	c/-1,sh/75
08-261	348.00	352.00	647139																				
08-261	352.00	356.00	647140																				
08-261	353.15	359.75			0.10	0.05	0.10	0.05	0.00	0.00	ol	M	W	N	M	W	N	N		gy	trspDu	tr,bksp	c/-1,sh/70
08-261	356.00	360.00	647141																				
08-261	359.75	369.95			4.00	0.10	4.10	0.50	0.00	va-0.05	ol	W	N	N	M	W	N	W		gy	trDu	tr,bksp	c/-1,sh/40
08-261	360.00	364.00	647142																				
08-261	364.00	368.00	647143																				
08-261	368.00	372.00	647144																				
08-261	369.95	375.30			5.00	0.10	5.00	0.50	0.00	va-0.05	ol	W	N	N	M	W	N	W		gy	trDu	tr,bksp	c/-1,sh/40
08-261	372.00	376.00	647145																				
08-261	375.30	391.80			5.00	0.30	5.30	0.50	0.00	va-0.1	ol	W	W	N	M	W	N	W		gy	trDu	tr,bksp	c/-1,sh/45
08-261	376.00	380.00	647146																				
08-261	380.00	384.00	647147																				
08-261	384.00	388.00	647148																				
08-261	388.00	392.00	647149																				
			647150	STD																			
			647151	STD																			
08-261	391.80	402.60			3.00	0.05	3.00	0.15	0.00	va-0.05	ol	W	W	N	M	W	N	M		gy	trgrDu	tr,gr	c/-1,sh/45
08-261	392.00	396.00	647152																				
08-261	396.00	400.00	647153																				
08-261	400.00	404.00	647154																				
08-261	402.60	411.25			1.00	0.05	1.00	0.10	0.00	0.00	ol	M	W	N	M	W	N	N		gy	trspDu	tr,bksp	c/-1
08-261	404.00	408.00	647155																				
08-261	408.00	412.00	647156																				
08-261	411.25	419.10			4.00	0.05	4.00	0.40	0.00	va-0.05	ol	M	W	N	M	W	N	W		gy	trspDu	tr,bksp	c/-1,sh/40
08-261	412.00	416.00	647157																				
08-261	416.00	419.10	647158																				

Hole 08-262

No Core

Hole 08-263

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-263	0.00	3.95																					
08-263	3.95	5.05			0.50	0.00	0.50	0.05	0.00	0.00	cpx	W	N	N	N	W	N	N	cb	gy	ocPx	bksp	f/60
08-263	5.05	11.10			4.00	0.00	4.00	0.10	0.00	0.00	ol	M	N	N	N	W	N	N		dkgy	spWH	bksp	c/-1,f/60
08-263	5.05	8.00	358707																				
08-263	8.00	12.00	358708																				
08-263	11.10	16.20			3.50	0.00	3.50	0.10	0.00	0.00	ol	M	N	N	N	W	N	N		dkgy	spDu	bksp	c/-1,f/45
08-263	12.00	16.00	358709																				
08-263	16.00	20.00	358710																				
08-263	16.20	26.15			1.00	0.00	1.00	0.05	0.00	0.00	ol	M	N	N	W	W	N	N		dkgy	spDu	bksp	c/-1,f/60
08-263	20.00	24.00	358711																				
08-263	24.00	28.00	358712																				
08-263	26.15	33.05			0.80	0.05	0.80	0.05	0.00	0.00	cpx	M	N	N	M	M	N	N	cb	gy-dkgy	sptrWh,trocPx	bksp	f/60,f/30
08-263	28.00	32.00	358713																				
08-263	32.00	36.00	358714																				
08-263	33.05	52.35			0.50	1.00	1.50	0.05	0.05	py-0.05	cpx	W	N	W	I	N	N	W	cb	ltgy	trocPx	tr	f/60,f/30
08-263	36.00	40.00	358715																				
08-263	40.00	44.00	358716																				
08-263	44.00	48.00	358717																				
08-263	48.00	52.00	358718																				
08-263	52.00	56.00	358719																				
			358720	B																			
08-263	52.35	57.90			1.00	0.50	1.50	0.05	0.10	py-0.05	cpx	M	N	N	M	W	N	W	cb	gy	trocPx,trspWh	tr,bksp	f/60
08-263	56.00	60.00	358721																				
08-263	57.90	67.95			0.50	4.00	4.50	0.05	0.05	py-0.05	cpx	W	N	N	M	W	N	M	cb	gy	trocPx	tr	f/80,c/-1
08-263	60.00	64.00	358722																				
08-263	64.00	68.00	358723																				
08-263	67.95	70.90			0.00	5.00	5.00	0.00	0.10	py-0.05	cpx	W	N	N	M	W	N	M	cb	dkgy	trocPx,GS	tr	f/60,sh/-1
08-263	68.00	72.00	358724																				
			358725	STD																			
			358726	STD																			
08-263	70.90	78.40			0.10	0.30	0.40	0.00	0.00	py-0.05	cpx	W	N	W	I	N	N	W	cb	gngy	trocPx	tr	f/60,f/20
08-263	72.00	76.00	358727																				
08-263	76.00	80.00	358728																				
08-263	78.40	81.45			0.00	3.00	3.00	0.00	0.05	py-0.05	ol	M	N	N	I	W	N	M	cb	dkgybn	trspWh,GS	tr,bksp	sh/60,sh/20
08-263	80.00	84.00	358729																				

SAMPLE DATA					SULPHIDES						SIL	MINERALOGY							GEOLOGY				
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FLT
08-263	81.45	83.60			1.50	1.00	2.50	0.05	0.00	va-0.1	ol	M	W	N	M	M	N	W		dkgy	sptrDu	bksp,tr	sh/45
08-263	83.60	102.30			0.10	1.00	1.10	0.00	0.05	0.00	cpx	W	N	N	I	N	N	W	cb	gy	trocPx	tr	f/45,f/-1
08-263	84.00	88.00	358730																				
08-263	88.00	92.00	358731																				
08-263	92.00	96.00	358732																				
08-263	96.00	100.00	358733																				
08-263	100.00	104.00	358734																				
08-263	102.30	112.90			1.00	2.00	3.00	0.10	0.10	0.00	cpx	W	N	N	I	N	N	W		dkgy	trocPx	tr	c/-1,f/60
08-263	104.00	108.00	358735																				
08-263	108.00	112.00	358736																				
08-263	112.00	116.00	358737																				
08-263	112.90	133.25			0.50	1.00	1.50	0.05	0.05	0.00	cpx	W	N	N	I	N	N	W		dkgy	trocPx	tr	c/-1,f/60
08-263	116.00	120.00	358738																				
08-263	120.00	124.00	358739																				
08-263	124.00	128.00	358740																				
08-263	128.00	132.00	358741																				
08-263	132.00	136.00	358742																				
08-263	133.25	135.30			0.10	0.00	0.10	0.00	0.00	0.00	ol	M	N	N	M	W	N	N		dkgy	sptrDu	bksp,tr	f/80
08-263	135.30	152.10			0.50	1.00	1.50	0.00	0.05	0.00	cpx	W	N	M	I	N	N	W		gngy	tlitrocPx	tr	f/60,c/-1
08-263	136.00	140.00	358743																				
08-263	140.00	144.00	358744																				
08-263	144.00	148.00	358745																				
08-263	148.00	152.10	358746																				

Hole 08-264

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	temoite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-264	0.00	2.75																					
08-264	2.75	7.90			0.50	0.05	0.50	0.05	0.00	0.00	cpx	W	N	N	M	M	N	N		gy	trocPx,Wh	tr,bksp	f/40
08-264	2.75	4.00	647159																				
			647160	B																			
08-264	4.00	8.00	647161																				
08-264	7.90	28.65			1.25	0.05	1.25	0.10	0.00	va-0.05	ol	M	W	N	M	M	N	N		gy	trspWh	tr,bksp	sh/70,c/-1
08-264	8.00	12.00	647162																				
08-264	12.00	16.00	647163																				
08-264	16.00	20.00	647164																				
08-264	20.00	24.00	647165																				
08-264	24.00	28.00	647166																				
08-264	28.00	32.00	647167																				
08-264	28.65	36.85			0.80	0.00	0.80	0.10	0.00	0.00	ol	W	N	N	M	W	N	N		gy	trWh	tr	c/-1,f/60
08-264	32.00	36.00	647168																				
08-264	36.00	40.00	647169																				
08-264	36.85	47.55			3.00	1.00	4.00	0.50	0.00	0.00	ol	I	W	N	M	I	N	N		bk	sptrWh	bksp,tr	f/45,f/60
08-264	40.00	44.00	647170																				
08-264	44.00	48.00	647171																				
08-264	47.55	54.60			2.00	0.00	2.00	0.10	0.00	0.00	ol	W	N	N	M	M	N	N		gy	trDu	tr,bksp	c/-1,f/30
08-264	48.00	52.00	647172																				
08-264	52.00	56.00	647173																				
08-264	54.60	64.15			6.00	0.00	6.00	0.60	0.00	0.00	ol	M	N	N	M	M	N	N		dkgy	trspDu	tr,bksp	c/-1,f/30
08-264	56.00	60.00	647174																				
			647175																				
			647176																				
08-264	60.00	64.00	647177																				
08-264	64.00	68.00	647178																				
08-264	64.15	70.75			8.00	0.05	8.00	0.40	0.00	0.00	bksp	I	N	N	M	I	N	N		bk	trSp	bksp	f/45
08-264	68.00	72.00	647179																				
08-264	70.75	74.45			5.00	1.00	6.00	1.00	0.00	0.00	ol	M	N	N	M	M	N	N		dkgy	trspDu	tr,bksp	f/60,c/-1
08-264	72.00	76.00	647180	D																			
08-264	74.45	79.90			3.50	0.50	4.00	0.80	0.00	0.00	ol	I	W	N	M	I	N	W		dkgy	sptrDu	bksp,tr	sh/60,sh/30
08-264	76.00	80.00	647181																				
08-264	79.90	86.70			5.00	1.00	6.00	0.80	0.05	0.00	ol	M	N	N	M	M	N	N		dkgy	trspDu	tr,bksp	c/-1,sh/60
08-264	80.00	84.00	647182																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	temoite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/bf/sh/FLT
08-264	84.00	88.00	647183																				
08-264	86.70	96.00			3.50	0.00	3.50	1.50	0.00	0.00	ol	W	N	N	W	W	N	N		gy	Du	bksp	c/-1
08-264	88.00	92.00	647184																				
08-264	92.00	96.00	647185																				
08-264	96.00	100.80			2.00	0.00	2.00	0.30	0.00	0.00	ol	W	N	N	W	W	N	N		gy	Du	bksp	c/-1
08-264	96.00	100.00	647186																				
08-264	100.00	104.00	647187																				
08-264	100.80	104.40			4.00	0.10	4.10	0.40	0.00	va-0.1	ol	W	W	N	W	W	N	N		gy	Du	bksp	c/-1
08-264	104.00	108.00	647188																				
08-264	104.40	116.50			3.00	0.00	3.00	0.30	0.00	0.00	ol	W	N	N	W	W	N	N		gy	Du	bksp	c/-1
08-264	108.00	112.00	647189																				
			647190	B																			
08-264	112.00	116.00	647191																				
08-264	116.00	120.00	647192																				
08-264	116.50	123.70			7.00	0.05	7.00	0.30	0.00	0.00	ol	W	N	N	W	W	N	N		gy	Du	bksp	c/-1
08-264	120.00	124.00	647193																				
08-264	123.70	126.55			0.40	0.00	0.40	0.08	0.00	0.00	ol	W	N	N	W	W	N	N		gy	Du	bksp	c/-1
08-264	124.00	128.00	647194																				
08-264	126.55	128.50			0.20	0.00	0.20	0.05	0.00	0.00	ol	M	W	W	W	W	N	N		dkgy	spDu	bksp	sh/30,sh/-1
08-264	128.00	132.00	647195																				
08-264	128.50	136.95			2.00	0.00	2.00	0.20	0.00	0.00	ol	W	N	N	W	W	N	N		gy	Du	bksp	c/-1,sh/40
08-264	132.00	136.00	647196																				
08-264	136.00	140.00	647197																				
08-264	136.95	145.25			4.00	0.00	4.00	0.40	0.00	0.00	ol	W	N	N	W	W	N	N		gy	Du	bksp	c/-1,sh/50
08-264	140.00	144.00	647198																				
08-264	144.00	148.00	647199																				
			647200	STD																			
			647201	STD																			
08-264	145.25	147.30			3.50	0.00	3.50	0.40	0.00	0.00	ol	M	W	N	W	M	N	N		dkgy	spDu	bksp	sh/50,sh/30
08-264	147.30	160.75			0.10	0.00	0.10	0.05	0.00	0.00	ol	W	W	N	W	W	N	N		gy	Du	bksp	sh/60,c/-1
08-264	148.00	152.00	647202																				
08-264	152.00	156.00	647203																				
08-264	156.00	160.00	647204																				
08-264	160.00	164.00	647205																				
08-264	160.00	164.00	647205																				
08-264	160.75	165.95			0.50	0.05	0.50	0.20	0.00	0.00	ol	W	W	N	W	W	N	N		gy	Du	bksp	c/-1,sh/30

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FL/T
08-264	164.00	168.00	647206																				
08-264	165.95	171.80			1.00	0.00	1.00	0.85	0.00	0.00	sp	I	W	N	W	M	N	N		bk	Sp	bksp	sh/-1
08-264	168.00	172.00	647207																				
08-264	171.80	173.85			7.00	0.00	7.00	0.10	0.00	0.00	sp	I	M	N	W	I	N	N		bk	Flt	bksp	sh/-1
08-264	172.00	176.00	647208																				
08-264	173.85	179.80			5.00	0.10	5.10	0.10	0.00	0.00	sp	I	W	N	W	I	N	N		bk	Sp	bksp	c/-1,sh/30
08-264	176.00	180.00	647209																				
08-264	179.80	182.25			0.30	0.00	0.30	0.05	0.00	0.00	sp	I	W	N	W	I	N	N		bk	Sp	bksp	c/-1
08-264	180.00	184.00	647210	D																			
08-264	182.25	188.15			1.00	0.20	1.20	0.05	0.00	0.00	sp	I	W	N	M	I	N	N		bk	sptrWh	bksp,tr	c/-1,sh/60
08-264	184.00	188.00	647211																				
08-264	188.00	192.00	647212																				
08-264	188.15	197.35			2.00	3.00	5.00	5.00	0.05	0.00	sp	I	W	N	M	M	N	W	cb	dkgy	sptrDu,trocPx	bksp,tr	sh/60,f/10
08-264	192.00	196.00	647213																				
08-264	196.00	200.00	647214																				
08-264	197.35	203.50			0.50	3.00	3.50	0.05	0.05	0.00	sp	I	W	N	M	M	N	W	cb	dkgy	Flt	bksp,tr	sh/60,f/-1
08-264	200.00	204.00	647215																				
08-264	203.50	208.00			0.50	0.20	0.70	0.05	0.00	0.00	ol	M	W	N	M	W	N	W		dkgy	trspDu	tr,bksp	f/60,sh/45
08-264	204.00	208.00	647216																				
08-264	208.00	212.40			0.00	3.00	3.00	0.00	0.05	0.00	cpx	N	N	N	M	N	N	M	chl	gnbn	altcPx	chl,tr	sh/60,f/30
08-264	208.00	212.00	647217																				
08-264	212.00	216.00	647218																				
08-264	212.40	218.10			0.00	0.05	0.05	0.05	0.00	0.00	ol	M	M	N	M	W	N	N		dkgy	sptrDu	sp,tr	sh/60,sh/-1
08-264	216.00	220.00	647219																				
			647220	B																			
08-264	218.10	223.50			0.00	0.05	0.05	0.00	0.00	0.00	ol	W	N	N	M	W	N	N		gngy	trDu	tr	c/-1,sh/45
08-264	220.00	224.00	647221																				
08-264	223.50	242.75			0.00	0.05	0.05	0.05	0.00	0.00	ol	W	N	N	M	W	N	N		gygn	trgDu	tr	c/-1
08-264	224.00	228.00	647222																				
08-264	228.00	232.00	647223																				
08-264	232.00	236.00	647224																				
			647225	STD																			
			647226	STD																			
08-264	236.00	240.00	647227																				
08-264	240.00	244.00	647228																				

SAMPLE DATA					SULPHIDES					SIL	MINERALOGY							GEOLOGY					
Hole #	From	To	Sample No.	QC/QA	% magmatic sulph	% non-magmatic sulph	% total sulph	% pn	% cpy	% other sulph	dominant silicate	black serpentine	other serpentine	talc	tremolite	magnetite	chromite	graphite	other min	color code	rock type	dominant alteration	structure c/b/f/sh/FLT
08-264	242.75	245.05			0.00	0.00	0.00	0.00	0.00	0.00	ol	W	W	W	M	W	N	N		gngy	trDu	tr	sh/35,sh/65
08-264	244.00	245.05	647229																				

Appendix C

Hole 08-249

Hole #	Depth /m	Azimuth /°	Inclination /°	Hole #	Depth /m	Azimuth /°	Inclination /°
08-249	0.00	180.0	-48.3	08-249	153.00	184.2	-49.4
08-249	3.00	180.1	-48.0	08-249	156.00	184.4	-49.4
08-249	6.00	180.2	-47.9	08-249	159.00	184.5	-49.4
08-249	9.00	180.2	-47.9	08-249	162.00	184.6	-49.5
08-249	12.00	180.2	-48.0	08-249	165.00	184.7	-49.5
08-249	15.00	180.2	-48.0	08-249	168.00	184.8	-49.6
08-249	18.00	180.3	-48.0	08-249	171.00	184.9	-49.6
08-249	21.00	180.3	-48.1	08-249	174.00	185.0	-49.6
08-249	24.00	180.4	-48.2	08-249	177.00	185.1	-49.7
08-249	27.00	180.6	-48.0	08-249	180.00	185.2	-49.7
08-249	30.00	180.8	-48.0	08-249	183.00	185.2	-49.6
08-249	33.00	180.9	-48.2	08-249	186.00	185.3	-49.6
08-249	36.00	181.0	-48.2	08-249	189.00	185.3	-49.6
08-249	39.00	181.2	-48.0	08-249	192.00	185.4	-49.6
08-249	42.00	181.3	-48.2	08-249	195.00	185.4	-49.6
08-249	45.00	181.4	-48.4	08-249	198.00	185.5	-49.6
08-249	48.00	181.5	-48.2	08-249	201.00	185.5	-49.7
08-249	51.00	181.6	-48.4	08-249	204.00	185.5	-49.7
08-249	54.00	181.7	-48.1	08-249	207.00	185.5	-49.7
08-249	57.00	181.8	-48.2	08-249	210.00	185.5	-49.8
08-249	60.00	181.8	-48.4	08-249	213.00	185.5	-49.9
08-249	63.00	181.9	-48.2	08-249	216.00	185.5	-49.9
08-249	66.00	182.0	-48.3	08-249	219.00	185.5	-49.9
08-249	69.00	182.1	-48.4	08-249	222.00	185.6	-49.9
08-249	72.00	182.3	-48.4	08-249	225.00	185.6	-50.0
08-249	75.00	182.4	-48.4	08-249	228.00	185.7	-50.0
08-249	78.00	182.5	-48.5	08-249	231.00	185.8	-50.1
08-249	81.00	182.5	-48.5	08-249	234.00	185.8	-50.2
08-249	84.00	182.6	-48.6	08-249	237.00	185.9	-50.1
08-249	87.00	182.7	-48.7	08-249	240.00	186.0	-50.2
08-249	90.00	182.7	-48.7	08-249	243.00	186.0	-50.3
08-249	93.00	182.8	-48.8	08-249	246.00	186.0	-50.3
08-249	96.00	182.8	-48.8	08-249	249.00	186.1	-50.4
08-249	99.00	182.8	-48.8	08-249	252.00	186.2	-50.4
08-249	102.00	182.9	-48.9	08-249	255.00	186.3	-50.4
08-249	105.00	182.9	-48.9	08-249	258.00	186.3	-50.4
08-249	108.00	182.9	-48.9	08-249	261.00	186.4	-50.4
08-249	111.00	183.0	-49.0	08-249	264.00	186.5	-50.3
08-249	114.00	183.0	-49.0	08-249	270.00	186.6	-50.4
08-249	117.00	183.1	-49.0				
08-249	120.00	183.1	-49.1				
08-249	123.00	183.2	-49.1				
08-249	126.00	183.4	-49.1				
08-249	129.00	183.5	-49.1				
08-249	132.00	183.6	-49.1				
08-249	135.00	183.6	-49.1				
08-249	138.00	183.7	-49.1				
08-249	141.00	183.8	-49.2				
08-249	144.00	183.9	-49.2				
08-249	147.00	184.0	-49.3				
08-249	150.00	184.1	-49.3				

Hole 08-250

Hole #	Depth /m	Azimuth /°	Inclination /°	Hole #	Depth /m	Azimuth /°	Inclination /°
08-250	0.00	181.4	-48.1	08-250	153.00	187.9	-46.1
08-250	3.00	181.5	-47.8	08-250	156.00	188.0	-46.2
08-250	6.00	181.6	-47.7	08-250	159.00	188.2	-46.2
08-250	9.00	181.6	-47.6	08-250	162.00	188.3	-46.2
08-250	12.00	181.6	-47.5	08-250	165.00	188.4	-46.2
08-250	15.00	181.7	-47.5	08-250	168.00	188.6	-46.3
08-250	18.00	181.8	-47.4	08-250	171.00	188.7	-46.3
08-250	21.00	181.8	-47.3	08-250	174.00	188.8	-46.4
08-250	24.00	181.9	-47.3	08-250	177.00	188.9	-46.4
08-250	27.00	182.0	-47.2				
08-250	30.00	182.1	-47.1				
08-250	33.00	182.2	-47.1				
08-250	36.00	182.3	-47.0				
08-250	39.00	182.4	-46.8				
08-250	42.00	182.4	-46.8				
08-250	45.00	182.5	-46.7				
08-250	48.00	182.6	-46.7				
08-250	51.00	182.7	-46.6				
08-250	54.00	182.8	-46.6				
08-250	57.00	182.9	-46.6				
08-250	60.00	183.0	-46.8				
08-250	63.00	183.2	-46.7				
08-250	66.00	183.4	-46.7				
08-250	69.00	183.5	-46.7				
08-250	72.00	183.7	-46.6				
08-250	75.00	183.9	-46.8				
08-250	78.00	184.0	-46.6				
08-250	81.00	184.2	-46.6				
08-250	84.00	184.4	-46.8				
08-250	87.00	184.6	-46.5				
08-250	90.00	184.8	-46.6				
08-250	93.00	185.0	-46.6				
08-250	96.00	185.2	-46.5				
08-250	99.00	185.4	-46.6				
08-250	102.00	185.6	-46.5				
08-250	105.00	185.8	-46.4				
08-250	108.00	186.0	-46.4				
08-250	111.00	186.1	-46.5				
08-250	114.00	186.3	-46.2				
08-250	117.00	186.5	-46.2				
08-250	120.00	186.7	-46.2				
08-250	123.00	186.8	-46.3				
08-250	126.00	186.9	-46.0				
08-250	129.00	187.0	-46.1				
08-250	132.00	187.1	-46.3				
08-250	135.00	187.2	-46.1				
08-250	138.00	187.4	-46.1				
08-250	141.00	187.5	-46.2				
08-250	144.00	187.6	-46.2				
08-250	147.00	187.6	-46.1				
08-250	150.00	187.8	-46.1				

Hole 08-251

No Downhole Survey

Hole 08-252

Hole #	Depth /m	Azimuth /°	Inclination /°	Hole #	Depth /m	Azimuth /°	Inclination /°
08-252	0.00	178.6	-48.7	08-252	153.00	184.9	-44.3
08-252	3.00	178.9	-48.9	08-252	156.00	185.0	-44.2
08-252	6.00	178.9	-49.0	08-252	159.00	185.1	-44.1
08-252	9.00	179.0	-49.0	08-252	162.00	185.1	-43.9
08-252	12.00	179.0	-49.0	08-252	165.00	185.2	-43.7
08-252	15.00	179.0	-49.0	08-252	168.00	185.4	-43.6
08-252	18.00	179.1	-48.9	08-252	171.00	185.5	-43.4
08-252	21.00	179.1	-48.8	08-252	174.00	185.6	-43.3
08-252	24.00	179.1	-48.7	08-252	177.00	185.7	-43.1
08-252	27.00	179.2	-48.5	08-252	180.00	185.8	-43.1
08-252	30.00	179.2	-48.4	08-252	183.00	185.9	-42.9
08-252	33.00	179.3	-48.3	08-252	186.00	186.0	-42.8
08-252	36.00	179.3	-48.2	08-252	189.00	186.1	-42.6
08-252	39.00	179.3	-48.1	08-252	192.00	186.3	-42.6
08-252	42.00	179.3	-48.0	08-252	195.00	186.4	-42.6
08-252	45.00	179.3	-47.9	08-252	198.00	186.6	-42.4
08-252	48.00	179.4	-47.7	08-252	201.00	186.8	-42.4
08-252	51.00	179.6	-47.7	08-252	204.00	187.0	-42.4
08-252	54.00	179.8	-47.7	08-252	207.00	187.2	-42.3
08-252	57.00	180.0	-47.6	08-252	213.00	187.6	-42.1
08-252	60.00	180.2	-47.5				
08-252	63.00	180.3	-47.4				
08-252	66.00	180.5	-47.3				
08-252	69.00	180.7	-47.2				
08-252	72.00	180.9	-47.0				
08-252	75.00	181.0	-46.9				
08-252	78.00	181.2	-46.8				
08-252	81.00	181.3	-46.7				
08-252	84.00	181.3	-46.7				
08-252	87.00	181.3	-46.5				
08-252	90.00	181.3	-46.3				
08-252	93.00	181.4	-46.2				
08-252	96.00	181.4	-46.2				
08-252	99.00	181.4	-46.0				
08-252	102.00	181.3	-45.9				
08-252	105.00	181.4	-45.7				
08-252	108.00	181.5	-45.5				
08-252	111.00	181.7	-45.5				
08-252	114.00	181.9	-45.3				
08-252	117.00	182.2	-45.3				
08-252	120.00	182.4	-45.2				
08-252	123.00	182.7	-45.1				
08-252	126.00	182.9	-45.0				
08-252	129.00	183.2	-44.9				
08-252	132.00	183.4	-44.8				
08-252	135.00	183.6	-44.8				
08-252	138.00	183.8	-44.6				
08-252	141.00	184.1	-44.5				
08-252	144.00	184.3	-44.5				
08-252	147.00	184.5	-44.4				
08-252	150.00	184.7	-44.4				

Hole 08-253

Hole #	Depth /m	Azimuth /°	Inclination /°	Hole #	Depth /m	Azimuth /°	Inclination /°
08-253	0.00	180.5	-49.9	08-253	153.00	186.3	-45.3
08-253	3.00	180.7	-49.9	08-253	156.00	186.4	-45.2
08-253	6.00	180.8	-49.8	08-253	159.00	186.5	-45.0
08-253	9.00	181.0	-49.7	08-253	162.00	186.6	-44.9
08-253	12.00	181.1	-49.6	08-253	165.00	186.7	-44.7
08-253	15.00	181.2	-49.6	08-253	168.00	186.8	-44.7
08-253	18.00	181.2	-49.5	08-253	171.00	187.0	-44.6
08-253	21.00	181.3	-49.5	08-253	174.00	187.1	-44.6
08-253	24.00	181.3	-49.3	08-253	177.00	187.3	-44.5
08-253	27.00	181.4	-49.1	08-253	180.00	187.5	-44.5
08-253	30.00	181.5	-49.1	08-253	183.00	187.6	-44.4
08-253	33.00	181.6	-49.0	08-253	186.00	187.7	-44.3
08-253	36.00	181.6	-48.9	08-253	189.00	187.9	-44.2
08-253	39.00	181.7	-48.7	08-253	192.00	188.0	-44.1
08-253	42.00	181.7	-48.6	08-253	195.00	188.2	-44.0
08-253	45.00	181.8	-48.4	08-253	198.00	188.3	-43.9
08-253	48.00	181.8	-48.3	08-253	201.00	188.5	-43.8
08-253	51.00	181.9	-48.2	08-253	204.00	188.5	-43.7
08-253	54.00	182.0	-48.0	08-253	207.00	188.6	-43.6
08-253	57.00	182.0	-47.9	08-253	210.00	188.7	-43.4
08-253	60.00	182.1	-47.8	08-253	213.00	188.8	-43.3
08-253	63.00	182.1	-47.7	08-253	216.00	188.9	-43.1
08-253	66.00	182.3	-47.6	08-253	219.00	189.0	-43.0
08-253	69.00	182.4	-47.7	08-253	222.00	189.2	-42.9
08-253	72.00	182.6	-47.7	08-253	225.00	189.3	-42.7
08-253	75.00	182.7	-47.7	08-253	228.00	189.4	-42.6
08-253	78.00	182.9	-47.7	08-253	231.00	189.6	-42.5
08-253	81.00	183.1	-47.6	08-253	234.00	189.8	-42.4
08-253	84.00	183.3	-47.6	08-253	237.00	189.9	-42.4
08-253	87.00	183.5	-47.5	08-253	240.00	190.1	-42.3
08-253	90.00	183.6	-47.5	08-253	243.00	190.2	-42.3
08-253	93.00	183.8	-47.4	08-253	246.00	190.3	-42.2
08-253	96.00	184.0	-47.3	08-253	249.00	190.4	-42.1
08-253	99.00	184.1	-47.2	08-253	255.00	190.7	-42.0
08-253	102.00	184.2	-47.2				
08-253	105.00	184.4	-47.1				
08-253	108.00	184.5	-46.9				
08-253	111.00	184.7	-46.9				
08-253	114.00	184.9	-46.9				
08-253	117.00	185.0	-46.8				
08-253	120.00	185.2	-46.7				
08-253	123.00	185.3	-46.7				
08-253	126.00	185.5	-46.6				
08-253	129.00	185.5	-46.5				
08-253	132.00	185.6	-46.3				
08-253	135.00	185.7	-46.2				
08-253	138.00	185.8	-46.1				
08-253	141.00	185.9	-45.9				
08-253	144.00	186.0	-45.8				
08-253	147.00	186.1	-45.6				
08-253	150.00	186.2	-45.5				

Hole 08-254

Hole #	Depth /m	Azimuth /°	Inclination /°	Hole #	Depth /m	Azimuth /°	Inclination /°
08-254	0.00	181.5	-48.9	08-254	153.00	187.3	-46.5
08-254	3.00	181.3	-48.6	08-254	156.00	187.2	-46.6
08-254	6.00	181.2	-48.5	08-254	159.00	187.2	-46.6
08-254	9.00	181.2	-48.4	08-254	162.00	187.1	-46.5
08-254	12.00	181.3	-48.3	08-254	165.00	187.0	-46.6
08-254	15.00	181.3	-48.3	08-254	168.00	186.9	-46.5
08-254	18.00	181.4	-48.2	08-254	171.00	186.9	-46.4
08-254	21.00	181.5	-48.2	08-254	174.00	186.8	-46.2
08-254	24.00	181.6	-48.1	08-254	177.00	186.9	-46.1
08-254	27.00	181.8	-48.1	08-254	180.00	187.1	-46.1
08-254	30.00	181.9	-48.1	08-254	183.00	187.4	-45.9
08-254	33.00	182.0	-48.2	08-254	186.00	187.6	-46.0
08-254	36.00	182.2	-48.2	08-254	189.00	187.8	-45.9
08-254	39.00	182.4	-48.0	08-254	192.00	188.0	-45.9
08-254	42.00	182.7	-48.0	08-254	195.00	188.1	-45.8
08-254	45.00	182.9	-47.9	08-254	198.00	188.2	-45.7
08-254	48.00	183.0	-47.9	08-254	201.00	188.3	-45.6
08-254	51.00	183.2	-47.9	08-254	204.00	188.4	-45.5
08-254	54.00	183.4	-47.8	08-254	207.00	188.4	-45.4
08-254	57.00	183.5	-47.8	08-254	210.00	188.4	-45.3
08-254	60.00	183.6	-47.8	08-254	213.00	188.3	-45.1
08-254	63.00	183.7	-47.8	08-254	216.00	188.3	-45.1
08-254	66.00	183.8	-47.8	08-254	219.00	188.3	-44.8
08-254	69.00	184.0	-47.9	08-254	222.00	188.3	-44.8
08-254	72.00	184.1	-47.8	08-254	225.00	188.3	-44.6
08-254	75.00	184.3	-47.8	08-254	228.00	188.3	-44.5
08-254	78.00	184.4	-47.9	08-254	231.00	188.4	-44.4
08-254	81.00	184.6	-47.8	08-254	234.00	188.4	-44.2
08-254	84.00	184.8	-47.8	08-254	237.00	188.6	-44.0
08-254	87.00	185.0	-47.8	08-254	240.00	188.7	-43.9
08-254	90.00	185.2	-47.7	08-254	243.00	188.9	-43.9
08-254	93.00	185.4	-47.7	08-254	246.00	189.1	-43.8
08-254	96.00	185.5	-47.6	08-254	249.00	189.3	-43.8
08-254	99.00	185.7	-47.6	08-254	252.00	189.5	-43.5
08-254	102.00	185.7	-47.5	08-254	255.00	189.7	-43.4
08-254	105.00	185.8	-47.4	08-254	258.00	189.9	-43.4
08-254	108.00	186.0	-47.3	08-254	261.00	190.0	-43.4
08-254	111.00	186.2	-47.4	08-254	264.00	190.2	-43.4
08-254	114.00	186.4	-47.2	08-254	267.00	190.3	-43.4
08-254	117.00	186.6	-47.3	08-254	270.00	190.5	-43.2
08-254	120.00	186.8	-47.1	08-254	273.00	190.7	-42.6
08-254	123.00	186.9	-47.1	08-254	276.00	191.0	-43.4
08-254	126.00	187.0	-47.1	08-254	282.00	191.2	-43.2
08-254	129.00	187.1	-47.2				
08-254	132.00	187.2	-47.1				
08-254	135.00	187.1	-47.0				
08-254	138.00	187.2	-46.9				
08-254	141.00	187.2	-46.8				
08-254	144.00	187.2	-46.7				
08-254	147.00	187.2	-46.6				
08-254	150.00	187.2	-46.5				

Hole 08-255

Hole #	Depth /m	Azimuth /°	Inclination /°	Hole #	Depth /m	Azimuth /°	Inclination /°
08-255	0.00	181.4	-51.0	08-255	153.00	181.9	-50.9
08-255	3.00	181.3	-50.8	08-255	156.00	182.0	-51.1
08-255	6.00	181.2	-50.8	08-255	159.00	182.1	-51.2
08-255	9.00	181.3	-50.8	08-255	162.00	182.3	-50.9
08-255	12.00	181.3	-50.7	08-255	165.00	182.4	-51.1
08-255	15.00	181.3	-50.7	08-255	168.00	182.4	-51.0
08-255	18.00	181.4	-50.7	08-255	171.00	182.5	-51.0
08-255	21.00	181.5	-50.7	08-255	174.00	182.7	-51.0
08-255	24.00	181.5	-50.7	08-255	177.00	182.8	-51.0
08-255	27.00	181.6	-50.7	08-255	180.00	182.9	-51.0
08-255	30.00	181.6	-50.7	08-255	183.00	183.0	-50.9
08-255	33.00	181.5	-50.8	08-255	186.00	183.1	-50.9
08-255	36.00	181.5	-50.9	08-255	189.00	183.1	-51.0
08-255	39.00	181.6	-50.6	08-255	192.00	183.2	-51.0
08-255	42.00	181.6	-50.8	08-255	195.00	183.2	-51.0
08-255	45.00	181.6	-50.8	08-255	198.00	183.3	-51.0
08-255	48.00	181.6	-50.9	08-255	201.00	183.4	-51.0
08-255	51.00	181.7	-51.0	08-255	204.00	183.6	-51.0
08-255	54.00	181.7	-50.9	08-255	207.00	183.7	-51.0
08-255	57.00	181.8	-51.0	08-255	210.00	183.8	-51.1
08-255	60.00	181.8	-51.1	08-255	213.00	183.9	-51.1
08-255	63.00	181.8	-51.0	08-255	216.00	184.1	-51.0
08-255	66.00	181.7	-51.0	08-255	219.00	184.2	-51.0
08-255	69.00	181.7	-51.0	08-255	222.00	184.3	-51.0
08-255	72.00	181.7	-51.1	08-255	225.00	184.4	-50.9
08-255	75.00	181.7	-51.0	08-255	228.00	184.5	-50.8
08-255	78.00	181.6	-51.1	08-255	231.00	184.6	-50.8
08-255	81.00	181.5	-51.0	08-255	234.00	184.7	-50.7
08-255	84.00	181.4	-51.0	08-255	237.00	184.8	-50.6
08-255	87.00	181.4	-51.0	08-255	240.00	184.9	-50.5
08-255	90.00	181.3	-51.0	08-255	243.00	185.0	-50.4
08-255	93.00	181.3	-50.9	08-255	246.00	185.1	-50.4
08-255	96.00	181.2	-50.9	08-255	249.00	185.2	-50.3
08-255	99.00	181.2	-50.7	08-255	252.00	185.4	-50.2
08-255	102.00	181.2	-50.7	08-255	255.00	185.5	-50.2
08-255	105.00	181.2	-50.8	08-255	258.00	185.6	-50.2
08-255	108.00	181.2	-50.8	08-255	261.00	185.8	-50.1
08-255	111.00	181.2	-49.2	08-255	264.00	185.9	-50.0
08-255	114.00	181.3	-50.8	08-255	267.00	186.0	-50.0
08-255	117.00	181.3	-50.8	08-255	270.00	186.2	-49.9
08-255	120.00	181.3	-50.7	08-255	273.00	186.3	-49.9
08-255	123.00	181.3	-50.8	08-255	276.00	186.4	-50.0
08-255	126.00	181.4	-51.0	08-255	279.00	186.5	-50.0
08-255	129.00	181.5	-51.4	08-255	282.00	186.5	-50.0
08-255	132.00	181.5	-50.3	08-255	285.00	186.6	-50.0
08-255	135.00	181.6	-50.9	08-255	288.00	186.6	-50.1
08-255	138.00	181.5	-51.2	08-255	291.00	186.7	-50.1
08-255	141.00	181.6	-50.9	08-255	294.00	186.8	-50.1
08-255	144.00	181.7	-51.0	08-255	297.00	186.8	-50.1
08-255	147.00	181.7	-50.9	08-255	300.00	186.9	-50.1
08-255	150.00	181.8	-51.0	08-255	303.00	186.9	-50.0

Hole #	Depth /m	Azimuth /°	Inclination /°
08-255	306.00	187.0	-50.0
08-255	309.00	187.1	-50.0
08-255	312.00	187.2	-49.9
08-255	315.00	187.3	-49.8
08-255	318.00	187.4	-49.8
08-255	321.00	187.5	-49.7
08-255	324.00	187.6	-49.7
08-255	330.00	187.8	-49.5

Hole 08-256

Hole #	Depth /m	Azimuth /°	Inclination /°	Hole #	Depth /m	Azimuth /°	Inclination /°
08-256	0.00	180.9	-50.0	08-256	153.00	184.8	-50.4
08-256	3.00	180.9	-49.9	08-256	156.00	184.9	-50.4
08-256	6.00	180.9	-50.0	08-256	159.00	185.0	-50.4
08-256	9.00	181.0	-50.0	08-256	162.00	185.1	-50.3
08-256	12.00	181.0	-50.0	08-256	165.00	185.2	-50.2
08-256	15.00	181.0	-50.1	08-256	168.00	185.3	-50.2
08-256	18.00	181.0	-50.1	08-256	171.00	185.3	-50.1
08-256	21.00	181.1	-50.2	08-256	174.00	185.4	-50.1
08-256	24.00	181.2	-50.2	08-256	177.00	185.4	-50.1
08-256	27.00	181.3	-50.2	08-256	180.00	185.5	-50.1
08-256	30.00	181.4	-50.3	08-256	183.00	185.6	-50.1
08-256	33.00	181.4	-50.3	08-256	186.00	185.8	-50.3
08-256	36.00	181.4	-50.4	08-256	189.00	185.8	-50.2
08-256	39.00	181.4	-50.4	08-256	192.00	185.9	-50.2
08-256	42.00	181.5	-50.4	08-256	195.00	185.9	-50.2
08-256	45.00	181.6	-50.4	08-256	198.00	186.0	-50.2
08-256	48.00	181.7	-50.5	08-256	201.00	186.0	-50.4
08-256	51.00	181.8	-50.4	08-256	204.00	186.0	-50.2
08-256	54.00	181.9	-50.4	08-256	207.00	185.9	-50.2
08-256	57.00	182.0	-50.4	08-256	210.00	185.9	-50.3
08-256	60.00	182.1	-50.4	08-256	213.00	185.9	-50.3
08-256	63.00	182.3	-50.4	08-256	216.00	185.8	-50.2
08-256	66.00	182.4	-50.3	08-256	219.00	185.8	-50.2
08-256	69.00	182.5	-50.2	08-256	222.00	185.9	-50.3
08-256	72.00	182.6	-50.3	08-256	225.00	185.8	-50.4
08-256	75.00	182.7	-50.2	08-256	228.00	185.7	-50.4
08-256	78.00	182.8	-50.2	08-256	231.00	185.7	-50.5
08-256	81.00	183.0	-50.2	08-256	234.00	185.7	-50.5
08-256	84.00	183.0	-50.3	08-256	237.00	185.7	-50.5
08-256	87.00	183.0	-50.2	08-256	240.00	185.8	-50.5
08-256	90.00	183.1	-50.2	08-256	243.00	185.9	-50.4
08-256	93.00	183.2	-50.2	08-256	249.00	186.1	-50.4
08-256	96.00	183.3	-50.2				
08-256	99.00	183.4	-50.1				
08-256	102.00	183.5	-50.1				
08-256	105.00	183.6	-50.2				
08-256	108.00	183.6	-50.2				
08-256	111.00	183.7	-50.2				
08-256	114.00	183.8	-50.2				
08-256	117.00	184.0	-50.2				
08-256	120.00	184.1	-50.2				
08-256	123.00	184.2	-50.3				
08-256	126.00	184.2	-50.3				
08-256	129.00	184.2	-50.4				
08-256	132.00	184.2	-50.6				
08-256	135.00	184.2	-50.5				
08-256	138.00	184.3	-50.4				
08-256	141.00	184.4	-50.6				
08-256	144.00	184.5	-50.4				
08-256	147.00	184.6	-50.4				
08-256	150.00	184.7	-50.4				

Hole 08-257

Hole #	Depth /m	Azimuth /°	Inclination /°	Hole #	Depth /m	Azimuth /°	Inclination /°
08-257	0.00	181.3	-49.4	08-257	153.00	183.6	-49.2
08-257	3.00	181.2	-49.5	08-257	156.00	183.5	-49.2
08-257	6.00	181.3	-49.4	08-257	159.00	183.4	-49.1
08-257	9.00	181.3	-49.3	08-257	162.00	183.4	-49.1
08-257	12.00	181.4	-49.3	08-257	165.00	183.3	-49.1
08-257	15.00	181.5	-49.2	08-257	168.00	183.3	-49.1
08-257	18.00	181.6	-49.2	08-257	171.00	183.2	-49.2
08-257	21.00	181.7	-49.1	08-257	174.00	183.1	-49.2
08-257	24.00	181.8	-49.2	08-257	177.00	183.1	-49.2
08-257	27.00	181.9	-49.2	08-257	180.00	183.1	-49.2
08-257	30.00	181.9	-49.2	08-257	183.00	183.1	-49.2
08-257	33.00	182.0	-49.2	08-257	186.00	183.1	-49.2
08-257	36.00	182.2	-49.2	08-257	189.00	183.0	-49.2
08-257	39.00	182.3	-49.1	08-257	192.00	183.0	-49.2
08-257	42.00	182.4	-49.0	08-257	195.00	183.0	-49.2
08-257	45.00	182.5	-49.0	08-257	198.00	182.9	-49.2
08-257	48.00	182.5	-49.0	08-257	201.00	182.8	-49.2
08-257	51.00	182.6	-48.9	08-257	204.00	182.8	-49.2
08-257	54.00	182.6	-49.0	08-257	207.00	182.8	-49.2
08-257	57.00	182.7	-49.0	08-257	210.00	182.7	-49.2
08-257	60.00	182.7	-48.9	08-257	213.00	182.7	-49.2
08-257	63.00	182.6	-48.9	08-257	216.00	182.7	-49.3
08-257	66.00	182.7	-48.9	08-257	219.00	182.8	-49.3
08-257	69.00	182.8	-48.9	08-257	222.00	182.7	-49.4
08-257	72.00	182.8	-48.9	08-257	225.00	182.7	-49.4
08-257	75.00	182.8	-49.0	08-257	228.00	182.7	-49.5
08-257	78.00	182.9	-49.0	08-257	231.00	182.7	-49.5
08-257	81.00	182.9	-48.9	08-257	234.00	182.7	-49.5
08-257	84.00	183.0	-49.0	08-257	237.00	182.7	-49.5
08-257	87.00	183.1	-49.0	08-257	240.00	182.7	-49.5
08-257	90.00	183.1	-49.0	08-257	243.00	182.8	-49.5
08-257	93.00	183.1	-49.1	08-257	246.00	182.8	-49.5
08-257	96.00	183.1	-49.1	08-257	249.00	182.8	-49.5
08-257	99.00	183.1	-49.0	08-257	252.00	182.9	-49.5
08-257	102.00	183.1	-49.1	08-257	255.00	182.9	-49.6
08-257	105.00	183.2	-49.0	08-257	258.00	183.1	-49.4
08-257	108.00	183.2	-49.0	08-257	264.00	183.3	-49.3
08-257	111.00	183.2	-49.0				
08-257	114.00	183.3	-49.0				
08-257	117.00	183.4	-49.0				
08-257	120.00	183.4	-49.0				
08-257	123.00	183.5	-49.0				
08-257	126.00	183.6	-49.1				
08-257	129.00	183.7	-49.3				
08-257	132.00	183.8	-49.1				
08-257	135.00	183.8	-49.1				
08-257	138.00	183.8	-49.1				
08-257	141.00	183.8	-49.1				
08-257	144.00	183.8	-49.2				
08-257	147.00	183.7	-49.2				
08-257	150.00	183.7	-49.2				

Hole 08-258

Hole #	Depth /m	Azimuth /°	Inclination /°	Hole #	Depth /m	Azimuth /°	Inclination /°
08-258	0.00	180.5	-51.8	08-258	153.00	185.7	-50.7
08-258	3.00	180.5	-51.7	08-258	156.00	185.9	-50.6
08-258	6.00	180.6	-51.7	08-258	159.00	186.0	-50.7
08-258	9.00	180.7	-51.7	08-258	162.00	186.1	-50.7
08-258	12.00	180.8	-51.7	08-258	165.00	186.2	-50.6
08-258	15.00	181.0	-51.7	08-258	168.00	186.3	-50.5
08-258	18.00	181.0	-51.8	08-258	171.00	186.3	-50.5
08-258	21.00	181.0	-51.7	08-258	174.00	186.3	-50.5
08-258	24.00	181.0	-51.7	08-258	177.00	186.4	-50.4
08-258	27.00	181.1	-51.7	08-258	180.00	186.4	-50.3
08-258	30.00	181.1	-51.7	08-258	183.00	186.5	-50.3
08-258	33.00	181.2	-51.6	08-258	186.00	186.5	-50.2
08-258	36.00	181.2	-51.6	08-258	189.00	186.6	-50.1
08-258	39.00	181.4	-51.7	08-258	192.00	186.6	-50.0
08-258	42.00	181.5	-51.6	08-258	195.00	186.7	-50.0
08-258	45.00	181.7	-51.5	08-258	198.00	186.8	-49.9
08-258	48.00	181.8	-51.5	08-258	201.00	187.0	-49.9
08-258	51.00	181.9	-51.5	08-258	204.00	187.1	-49.9
08-258	54.00	182.0	-51.5	08-258	207.00	187.3	-49.9
08-258	57.00	182.0	-51.5	08-258	210.00	187.4	-49.9
08-258	60.00	182.0	-51.5	08-258	213.00	187.5	-49.9
08-258	63.00	182.0	-51.7	08-258	216.00	187.6	-49.9
08-258	66.00	182.0	-51.6	08-258	219.00	187.7	-49.9
08-258	69.00	182.1	-51.6	08-258	222.00	187.9	-49.8
08-258	72.00	182.2	-51.7	08-258	225.00	188.0	-49.8
08-258	75.00	182.3	-51.7	08-258	228.00	188.1	-49.7
08-258	78.00	182.4	-51.7	08-258	231.00	188.3	-49.6
08-258	81.00	182.6	-51.7	08-258	234.00	188.4	-49.6
08-258	84.00	182.7	-51.7	08-258	237.00	188.6	-49.6
08-258	87.00	182.8	-51.7	08-258	240.00	188.7	-49.6
08-258	90.00	182.9	-51.7	08-258	243.00	188.9	-49.6
08-258	93.00	183.0	-51.6	08-258	246.00	189.0	-49.5
08-258	96.00	183.1	-51.5	08-258	249.00	189.2	-49.5
08-258	99.00	183.2	-51.4	08-258	252.00	189.4	-49.5
08-258	102.00	183.4	-51.3	08-258	255.00	189.5	-49.4
08-258	105.00	183.5	-51.2	08-258	258.00	189.6	-49.4
08-258	108.00	183.6	-51.1	08-258	261.00	189.8	-49.2
08-258	111.00	183.7	-51.1	08-258	264.00	190.0	-49.3
08-258	114.00	183.9	-51.1	08-258	267.00	190.1	-49.1
08-258	117.00	184.0	-51.1	08-258	273.00	190.4	-49.0
08-258	120.00	184.2	-51.0				
08-258	123.00	184.4	-50.9				
08-258	126.00	184.5	-50.9				
08-258	129.00	184.7	-51.0				
08-258	132.00	184.8	-51.0				
08-258	135.00	184.9	-50.9				
08-258	138.00	185.1	-50.8				
08-258	141.00	185.2	-50.8				
08-258	144.00	185.3	-50.7				
08-258	147.00	185.4	-50.7				
08-258	150.00	185.5	-50.8				

Hole 08-259

Hole #	Depth /m	Azimuth /°	Inclination /°	Hole #	Depth /m	Azimuth /°	Inclination /°
08-259	0.00	180.9	-48.8	08-259	153.00	185.5	-47.9
08-259	3.00	180.9	-48.9	08-259	156.00	185.6	-47.9
08-259	6.00	180.9	-48.8	08-259	159.00	185.6	-47.7
08-259	9.00	181.0	-48.8	08-259	162.00	185.8	-47.6
08-259	12.00	181.1	-48.9	08-259	165.00	185.9	-47.5
08-259	15.00	181.1	-48.9	08-259	168.00	186.0	-47.3
08-259	18.00	181.1	-48.9	08-259	171.00	186.1	-47.2
08-259	21.00	181.1	-48.9	08-259	174.00	186.2	-47.1
08-259	24.00	181.1	-49.0	08-259	177.00	186.3	-47.0
08-259	27.00	181.2	-49.1	08-259	180.00	186.4	-46.9
08-259	30.00	181.3	-49.1	08-259	183.00	186.5	-46.7
08-259	33.00	181.3	-49.1	08-259	186.00	186.6	-46.7
08-259	36.00	181.4	-49.1	08-259	189.00	186.7	-46.6
08-259	39.00	181.5	-49.1	08-259	192.00	186.8	-46.5
08-259	42.00	181.6	-49.1	08-259	195.00	187.0	-46.4
08-259	45.00	181.8	-49.1	08-259	198.00	187.2	-46.3
08-259	48.00	182.0	-49.2	08-259	201.00	187.3	-46.2
08-259	51.00	182.1	-49.2	08-259	204.00	187.5	-46.1
08-259	54.00	182.3	-49.2	08-259	207.00	187.7	-46.0
08-259	57.00	182.4	-49.3	08-259	210.00	187.8	-46.0
08-259	60.00	182.6	-49.3	08-259	213.00	188.0	-45.9
08-259	63.00	182.7	-49.3	08-259	216.00	188.1	-45.8
08-259	66.00	182.8	-49.3	08-259	219.00	188.2	-45.7
08-259	69.00	182.9	-49.3	08-259	222.00	188.4	-45.5
08-259	72.00	183.0	-49.3	08-259	225.00	188.5	-45.4
08-259	75.00	183.2	-49.3	08-259	228.00	188.6	-45.3
08-259	78.00	183.3	-49.3	08-259	231.00	188.7	-45.2
08-259	81.00	183.4	-49.3	08-259	234.00	188.8	-45.1
08-259	84.00	183.5	-49.4	08-259	237.00	188.9	-44.9
08-259	87.00	183.5	-49.2	08-259	240.00	188.9	-44.9
08-259	90.00	183.6	-49.1	08-259	243.00	189.0	-44.7
08-259	93.00	183.6	-49.0	08-259	246.00	189.0	-44.6
08-259	96.00	183.7	-48.8	08-259	249.00	189.1	-44.5
08-259	99.00	183.7	-48.7	08-259	252.00	189.2	-44.4
08-259	102.00	183.7	-48.6	08-259	255.00	189.3	-44.3
08-259	105.00	183.9	-48.5	08-259	258.00	189.3	-44.2
08-259	108.00	184.0	-48.5	08-259	261.00	189.3	-44.0
08-259	111.00	184.2	-48.4	08-259	264.00	189.4	-43.9
08-259	114.00	184.3	-48.4	08-259	267.00	189.4	-43.7
08-259	117.00	184.4	-48.4	08-259	270.00	189.5	-43.6
08-259	120.00	184.5	-48.4	08-259	273.00	189.6	-43.5
08-259	123.00	184.6	-48.3	08-259	276.00	189.6	-43.4
08-259	126.00	184.7	-48.2	08-259	279.00	189.7	-43.2
08-259	129.00	184.7	-48.1	08-259	282.00	189.8	-43.1
08-259	132.00	184.8	-48.0	08-259	285.00	189.9	-43.1
08-259	135.00	184.9	-48.0	08-259	291.00	190.0	-42.9
08-259	138.00	184.9	-47.9				
08-259	141.00	185.0	-47.9				
08-259	144.00	185.2	-48.0				
08-259	147.00	185.2	-48.0				
08-259	150.00	185.4	-47.9				

Hole 08-260

Hole #	Depth /m	Azimuth /°	Inclination /°	Hole #	Depth /m	Azimuth /°	Inclination /°
08-260	0.00	178.6	-50.2	08-260	153.00	181.4	-51.2
08-260	3.00	178.8	-50.3	08-260	156.00	181.5	-51.2
08-260	6.00	178.9	-50.3	08-260	159.00	181.4	-51.2
08-260	9.00	178.9	-50.2	08-260	162.00	181.6	-51.2
08-260	12.00	179.0	-50.3	08-260	165.00	181.5	-51.2
08-260	15.00	179.1	-50.3	08-260	168.00	181.5	-51.2
08-260	18.00	179.2	-50.4	08-260	171.00	181.5	-51.3
08-260	21.00	179.3	-50.4	08-260	174.00	181.5	-51.2
08-260	24.00	179.5	-50.5	08-260	177.00	181.4	-51.2
08-260	27.00	179.6	-50.5	08-260	180.00	181.4	-51.3
08-260	30.00	179.7	-50.5	08-260	183.00	181.5	-51.2
08-260	33.00	179.7	-50.5	08-260	186.00	181.4	-51.3
08-260	36.00	179.7	-50.5	08-260	189.00	181.5	-51.2
08-260	39.00	179.8	-50.5	08-260	192.00	181.4	-51.2
08-260	42.00	179.8	-50.6	08-260	195.00	181.4	-51.3
08-260	45.00	179.9	-50.6	08-260	198.00	181.3	-51.4
08-260	48.00	180.0	-50.7	08-260	201.00	181.2	-51.4
08-260	51.00	180.0	-50.7	08-260	204.00	181.2	-51.4
08-260	54.00	180.0	-50.7	08-260	207.00	181.1	-51.4
08-260	57.00	180.1	-50.8	08-260	210.00	181.1	-51.3
08-260	60.00	180.1	-50.9	08-260	213.00	181.1	-51.2
08-260	63.00	180.2	-51.0	08-260	216.00	181.0	-51.2
08-260	66.00	180.2	-51.0	08-260	219.00	181.0	-51.2
08-260	69.00	180.2	-51.1	08-260	222.00	181.0	-51.2
08-260	72.00	180.3	-51.0	08-260	225.00	181.0	-51.2
08-260	75.00	180.3	-51.0	08-260	228.00	181.0	-51.1
08-260	78.00	180.3	-51.1	08-260	231.00	181.1	-51.2
08-260	81.00	180.4	-51.1	08-260	234.00	181.1	-51.2
08-260	84.00	180.4	-51.2	08-260	237.00	181.2	-51.2
08-260	87.00	180.4	-51.3	08-260	240.00	181.2	-51.1
08-260	90.00	180.4	-51.3	08-260	243.00	181.3	-51.2
08-260	93.00	180.4	-51.4	08-260	246.00	181.3	-51.2
08-260	96.00	180.5	-51.4	08-260	249.00	181.4	-51.2
08-260	99.00	180.5	-51.4	08-260	252.00	181.4	-51.2
08-260	102.00	180.5	-51.4	08-260	255.00	181.4	-51.2
08-260	105.00	180.5	-51.3	08-260	258.00	181.5	-51.2
08-260	108.00	180.5	-51.3	08-260	261.00	181.6	-51.2
08-260	111.00	180.6	-51.3	08-260	264.00	181.6	-51.2
08-260	114.00	180.7	-51.2	08-260	267.00	181.7	-51.2
08-260	117.00	180.8	-51.4	08-260	270.00	181.7	-51.2
08-260	120.00	180.8	-51.3	08-260	273.00	181.8	-51.2
08-260	123.00	180.9	-51.2	08-260	276.00	181.8	-51.3
08-260	126.00	181.0	-51.3	08-260	279.00	181.8	-51.3
08-260	129.00	180.9	-51.2	08-260	282.00	181.9	-51.2
08-260	132.00	181.0	-51.2	08-260	285.00	181.9	-51.3
08-260	135.00	181.1	-51.2	08-260	288.00	181.9	-51.3
08-260	138.00	181.1	-51.3	08-260	291.00	181.9	-51.4
08-260	141.00	181.2	-51.2	08-260	294.00	182.0	-51.4
08-260	144.00	181.2	-51.2	08-260	297.00	182.0	-51.4
08-260	147.00	181.3	-51.2	08-260	300.00	182.0	-51.4
08-260	150.00	181.3	-51.2	08-260	303.00	182.0	-51.4

Hole #	Depth /m	Azimuth /°	Inclination /°
08-260	306.00	182.1	-51.5
08-260	309.00	182.1	-51.4
08-260	312.00	182.2	-51.5
08-260	315.00	182.2	-51.5
08-260	318.00	182.3	-51.5
08-260	324.00	182.3	-51.5

Hole 08-261

Hole #	Depth /m	Azimuth /°	Inclination /°	Hole #	Depth /m	Azimuth /°	Inclination /°
08-261	0.00	178.7	-50.7	08-261	153.00	178.6	-51.1
08-261	3.00	178.6	-50.7	08-261	156.00	178.7	-51.0
08-261	6.00	178.6	-50.7	08-261	159.00	178.8	-51.0
08-261	9.00	178.6	-50.7	08-261	162.00	178.9	-51.0
08-261	12.00	178.6	-50.7	08-261	165.00	179.0	-50.9
08-261	15.00	178.6	-50.6	08-261	168.00	179.1	-50.9
08-261	18.00	178.5	-50.6	08-261	171.00	179.2	-50.9
08-261	21.00	178.4	-50.6	08-261	174.00	179.3	-50.9
08-261	24.00	178.3	-50.6	08-261	177.00	179.4	-50.9
08-261	27.00	178.2	-50.5	08-261	180.00	179.4	-50.9
08-261	30.00	178.2	-50.6	08-261	183.00	179.5	-50.9
08-261	33.00	178.1	-50.5	08-261	186.00	179.6	-50.9
08-261	36.00	178.0	-50.5	08-261	189.00	179.6	-50.9
08-261	39.00	178.0	-50.5	08-261	192.00	179.7	-50.9
08-261	42.00	177.9	-50.5	08-261	195.00	179.7	-50.9
08-261	45.00	177.8	-50.5	08-261	198.00	179.8	-51.0
08-261	48.00	177.6	-50.5	08-261	201.00	179.9	-50.8
08-261	51.00	177.4	-50.5	08-261	204.00	180.0	-50.9
08-261	54.00	177.2	-50.5	08-261	207.00	180.1	-50.9
08-261	57.00	177.2	-50.6	08-261	210.00	180.1	-51.0
08-261	60.00	177.2	-50.6	08-261	213.00	180.2	-51.0
08-261	63.00	177.1	-50.6	08-261	216.00	180.3	-51.0
08-261	66.00	177.1	-50.7	08-261	219.00	180.4	-51.1
08-261	69.00	177.1	-50.7	08-261	222.00	180.5	-51.1
08-261	72.00	177.1	-50.8	08-261	225.00	180.6	-51.1
08-261	75.00	177.1	-50.9	08-261	228.00	180.7	-51.1
08-261	78.00	177.1	-50.9	08-261	231.00	180.8	-51.1
08-261	81.00	176.9	-51.0	08-261	234.00	180.8	-51.1
08-261	84.00	176.8	-51.0	08-261	237.00	180.9	-51.0
08-261	87.00	176.7	-51.1	08-261	240.00	181.0	-51.0
08-261	90.00	176.7	-51.1	08-261	243.00	181.1	-51.0
08-261	93.00	176.7	-51.1	08-261	246.00	181.1	-51.0
08-261	96.00	176.8	-51.1	08-261	249.00	181.2	-51.0
08-261	99.00	176.8	-51.0	08-261	252.00	181.4	-50.9
08-261	102.00	176.9	-51.0	08-261	255.00	181.4	-51.0
08-261	105.00	176.9	-51.2	08-261	258.00	181.6	-50.9
08-261	108.00	176.9	-51.0	08-261	261.00	181.7	-50.9
08-261	111.00	177.0	-51.2	08-261	264.00	181.8	-50.9
08-261	114.00	177.0	-51.1	08-261	267.00	181.9	-50.9
08-261	117.00	177.1	-51.1	08-261	270.00	181.9	-50.9
08-261	120.00	177.1	-51.1	08-261	273.00	182.0	-50.9
08-261	123.00	177.2	-51.1	08-261	276.00	182.0	-50.8
08-261	126.00	177.4	-51.1	08-261	279.00	182.2	-50.8
08-261	129.00	177.5	-51.1	08-261	282.00	182.2	-50.8
08-261	132.00	177.6	-51.2	08-261	285.00	182.3	-50.8
08-261	135.00	177.7	-51.1	08-261	288.00	182.4	-50.7
08-261	138.00	177.8	-51.2	08-261	291.00	182.5	-50.6
08-261	141.00	178.0	-51.1	08-261	294.00	182.6	-50.6
08-261	144.00	178.1	-51.1	08-261	297.00	182.7	-50.5
08-261	147.00	178.3	-51.1	08-261	300.00	182.8	-50.5
08-261	150.00	178.4	-51.1	08-261	303.00	182.9	-50.4

Hole #	Depth /m	Azimuth /°	Inclination /°
08-261	306.00	182.9	-50.3
08-261	309.00	183.0	-50.3
08-261	312.00	183.0	-50.3
08-261	315.00	183.0	-50.4
08-261	318.00	183.0	-50.4
08-261	321.00	183.1	-50.5
08-261	324.00	183.1	-50.5
08-261	327.00	183.1	-50.5
08-261	330.00	183.1	-50.6
08-261	333.00	183.1	-50.6
08-261	336.00	183.2	-50.7
08-261	339.00	183.2	-50.6
08-261	342.00	183.2	-50.5
08-261	345.00	183.3	-50.5
08-261	348.00	183.4	-50.5
08-261	351.00	183.5	-50.4
08-261	357.00	183.5	-50.4

Hole 08-262

No Downhole Survey


Hole 08-263


Hole #	Depth /m	Azimuth /°	Inclination /°
08-263	0.00	180.0	-89.0
08-263	3.00	179.3	-88.9
08-263	6.00	176.0	-89.0
08-263	9.00	177.5	-88.9
08-263	12.00	177.2	-88.9
08-263	15.00	175.7	-89.0
08-263	18.00	175.2	-88.8
08-263	21.00	173.1	-88.8
08-263	24.00	174.0	-88.7
08-263	27.00	173.5	-88.7
08-263	30.00	172.1	-88.7
08-263	33.00	173.2	-88.8
08-263	36.00	169.3	-88.9
08-263	39.00	168.2	-88.7
08-263	42.00	165.5	-88.9
08-263	45.00	163.3	-88.9
08-263	48.00	163.3	-88.9
08-263	51.00	163.7	-88.9
08-263	54.00	163.3	-88.9
08-263	57.00	163.1	-88.8
08-263	60.00	165.7	-88.8
08-263	63.00	164.1	-88.9
08-263	66.00	166.0	-88.8
08-263	69.00	165.7	-88.8
08-263	72.00	164.9	-88.8
08-263	75.00	165.0	-88.9
08-263	78.00	165.5	-88.9
08-263	81.00	169.1	-88.7
08-263	84.00	170.2	-88.9
08-263	87.00	168.8	-88.9
08-263	90.00	168.4	-88.8
08-263	93.00	168.1	-88.8
08-263	96.00	166.2	-88.9
08-263	99.00	167.5	-88.9
08-263	102.00	169.5	-88.9
08-263	105.00	167.5	-89.0
08-263	108.00	166.3	-88.9
08-263	111.00	163.8	-89.1
08-263	114.00	162.8	-89.0
08-263	117.00	164.0	-89.0
08-263	120.00	161.7	-89.1
08-263	123.00	161.2	-89.0
08-263	126.00	159.7	-89.0
08-263	129.00	158.3	-89.1
08-263	132.00	156.8	-89.0
08-263	135.00	157.2	-88.9
08-263	141.00	155.7	-88.9

Hole 08-264

Hole #	Depth /m	Azimuth /°	Inclination /°	Hole #	Depth /m	Azimuth /°	Inclination /°
08-264	0.00	358.3	-4.5	08-264	153.00	358.5	-4.5
08-264	3.00	358.3	-4.4	08-264	156.00	358.5	-4.5
08-264	6.00	358.4	-4.5	08-264	159.00	358.5	-4.4
08-264	9.00	358.3	-4.5	08-264	162.00	358.5	-4.5
08-264	12.00	358.3	-4.6	08-264	165.00	358.5	-4.5
08-264	15.00	358.3	-4.6	08-264	168.00	358.5	-4.5
08-264	18.00	358.3	-4.6	08-264	171.00	358.4	-4.5
08-264	21.00	358.4	-4.6	08-264	174.00	358.4	-4.6
08-264	24.00	358.4	-4.6	08-264	177.00	358.4	-4.5
08-264	27.00	358.5	-4.5	08-264	180.00	358.4	-4.5
08-264	30.00	358.5	-4.5	08-264	183.00	358.4	-4.3
08-264	33.00	358.6	-4.4	08-264	186.00	358.4	-4.5
08-264	36.00	358.7	-4.3	08-264	189.00	358.4	-4.6
08-264	39.00	358.7	-4.2	08-264	192.00	358.4	-4.6
08-264	42.00	358.8	-4.2	08-264	195.00	358.4	-4.6
08-264	45.00	358.9	-4.2	08-264	198.00	358.4	-4.7
08-264	48.00	358.9	-4.2	08-264	201.00	358.3	-4.5
08-264	51.00	359.0	-4.2	08-264	204.00	358.3	-4.6
08-264	54.00	359.1	-4.3	08-264	207.00	358.3	-4.7
08-264	57.00	359.3	-4.3	08-264	210.00	358.2	-4.9
08-264	60.00	359.4	-4.4	08-264	213.00	358.2	-4.5
08-264	63.00	359.5	-4.3	08-264	216.00	358.2	-4.7
08-264	66.00	359.6	-4.4	08-264	219.00	358.1	-4.3
08-264	69.00	359.6	-4.4	08-264	222.00	358.1	-4.9
08-264	72.00	359.7	-4.4	08-264	225.00	358.0	-4.9
08-264	75.00	359.8	-4.5	08-264	228.00	358.0	-4.9
08-264	78.00	359.8	-4.4	08-264	234.00	357.9	-4.9
08-264	81.00	359.8	-4.2				
08-264	84.00	359.7	-4.2				
08-264	87.00	359.7	-4.3				
08-264	90.00	359.6	-4.2				
08-264	93.00	359.6	-4.3				
08-264	96.00	359.6	-4.3				
08-264	99.00	359.6	-5.1				
08-264	102.00	359.5	-4.3				
08-264	105.00	359.5	-4.4				
08-264	108.00	359.4	-4.4				
08-264	111.00	359.3	-4.4				
08-264	114.00	359.2	-4.4				
08-264	117.00	359.1	-4.5				
08-264	120.00	359.1	-4.6				
08-264	123.00	359.0	-4.4				
08-264	126.00	359.0	-4.5				
08-264	129.00	358.9	-4.4				
08-264	132.00	358.8	-4.4				
08-264	135.00	358.7	-4.5				
08-264	138.00	358.6	-4.4				
08-264	141.00	358.6	-4.4				
08-264	144.00	358.6	-4.4				
08-264	147.00	358.5	-4.4				
08-264	150.00	358.5	-4.4				

Appendix D





Legend

	Dunite, serpentinized dunite, and serpentinite		Green dunite and serpentinized green dunite
	Wehrlite and serpentinized wehrlite		Olivine clinopyroxenite and clinopyroxenite
	Hornblende clinopyroxenite, magnetite clinopyroxenite		Hornblende and feldspathic hornblende
	Hornfels, calc-silicate, inclusion		Dikes of: diorite, granodiorite, hornblende, felspathic hornblende; undifferentiated
	Phyllite		>0.1 % sulphide Ni grade envelope
	>0.2 % sulphide Ni grade envelope		>0.3 % sulphide Ni grade envelope


Note: Cross sections with no 0.1 % grade envelopes either do not contain enough information for interpretation, or the space between 0.2 % grade envelopes is all above 0.1 % sulphide Ni.



Downhole Data Legend

	0 - 100		0.1 - 0.2		0 - 5
	100 - 500		0.2 - 0.3		5 - 12
	500 - 1000		0.3 - 0.5		12 - 20
	1000 - 3600		0.5 - 5		20 - 25
					25 - 35

Legend for HoleID: tdMg, logged geology, acNi, Pt+Pd, EOH



0 25 50 metres Scale 1:2,000

Legend

	Dunite, serpentinized dunite, and serpentinite		Green dunite and serpentinized green dunite
	Wehrlite and serpentinized wehrlite		Olivine clinopyroxenite and clinopyroxenite
	Hornblende clinopyroxenite, magnetite clinopyroxenite		Hornblende and feldspathic hornblende
	Hornfels, calc-silicate, inclusion		Dikes of: diorite, granodiorite, hornblende, felspathic hornblende; undifferentiated
	Phyllite		>0.1 % sulphide Ni grade envelope
	>0.2 % sulphide Ni grade envelope		>0.3 % sulphide Ni grade envelope


Note: Cross sections with no 0.1 % grade envelopes either do not contain enough information for interpretation, or the space between 0.2 % grade envelopes is all above 0.1 % sulphide Ni.

Downhole Data Legend

	0 - 100		0 - 0.1		0 - 5
	100 - 500		0.1 - 0.2		5 - 12
	500 - 1000		0.2 - 0.3		12 - 20
	1000 - 3600		0.3 - 0.5		20 - 25
			0.5 - 5		25 - 35

Legend for Downhole Data Legend:

- HoleID
- tdMg
- logged geology
- acNi
- Pt+Pd
- EOH



Legend

	Dunite, serpentinized dunite, and serpentinite		Green dunite and serpentinized green dunite
	Wehrilite and serpentinized wehrilite		Olivine clinopyroxenite and clinopyroxenite
	Hornblende clinopyroxenite, magnetite clinopyroxenite		Hornblende and feldspathic hornblende
	Hornfels, calc-silicate, inclusion		Dikes of: diorite, granodiorite, hornblende, felspathic hornblende; undifferentiated
	Phyllite		>0.1 % sulphide Ni grade envelope
	>0.2 % sulphide Ni grade envelope		>0.3 % sulphide Ni grade envelope

Note: Cross sections with no 0.1 % grade envelopes either do not contain enough information for interpretation, or the space between 0.2 % grade envelopes is all above 0.1 % sulphide Ni.


Downhole Data Legend

	0 - 100		0 - 0.1		0 - 5
	100 - 500		0.1 - 0.2		5 - 12
	500 - 1000		0.2 - 0.3		12 - 20
	1000 - 3600		0.3 - 0.5		20 - 25
			0.5 - 5		25 - 35

Legend for Downhole Data Legend:

- Pt+Pd (ppb)**: 0 - 100, 100 - 500, 500 - 1000, 1000 - 3600
- acNi (%)**: 0 - 0.1, 0.1 - 0.2, 0.2 - 0.3, 0.3 - 0.5, 0.5 - 5
- tdMg (%)**: 0 - 5, 5 - 12, 12 - 20, 20 - 25, 25 - 35

Vertical axis labels: HoleID, tdMg, logged geology, acNi, Pt+Pd, EOH



Legend

	Dunite, serpentinized dunite, and serpentinite		Green dunite and serpentinized green dunite
	Wehrlite and serpentinized wehrlite		Olivine clinopyroxenite and clinopyroxenite
	Hornblende clinopyroxenite, magnetite clinopyroxenite		Hornblende and feldspathic hornblende
	Hornfels, calc-silicate, inclusion		Dikes of: diorite, granodiorite, hornblende, feldspathic hornblende; undifferentiated
	Phyllite		>0.1 % sulphide Ni grade envelope
	>0.2 % sulphide Ni grade envelope		>0.3 % sulphide Ni grade envelope

Note: Cross sections with no 0.1 % grade envelopes either do not contain enough information for interpretation, or the space between 0.2 % grade envelopes is all above 0.1 % sulphide Ni.

Downhole Data Legend

	0 - 100		0 - 0.1		0 - 5
	100 - 500		0.1 - 0.2		5 - 12
	500 - 1000		0.2 - 0.3		12 - 20
	1000 - 3600		0.3 - 0.5		20 - 25
			0.5 - 5		25 - 35



Legend for Downhole Data Legend:

- tdMg (ppb): 0 - 100, 100 - 500, 500 - 1000, 1000 - 3600
- acNi (%): 0 - 0.1, 0.1 - 0.2, 0.2 - 0.3, 0.3 - 0.5, 0.5 - 5
- tdMg (%): 0 - 5, 5 - 12, 12 - 20, 20 - 25, 25 - 35

Legend for Downhole Data Legend (Geology):

- tdMg
- logged geology
- acNi
- Pt+Pd
- EOH

Scale 1:2,000



Legend

Dunite, serpentinized dunite, and serpentinite	Green dunite and serpentinized green dunite
Wehrlite and serpentinized wehrlite	Olivine clinopyroxenite and clinopyroxenite
Hornblende clinopyroxenite, magnetite clinopyroxenite	Hornblende and feldspathic hornblende
Hornfels, calc-silicate, inclusion	Dikes of: diorite, granodiorite, hornblende, feldspathic hornblende; undifferentiated
Phyllite	>0.1 % sulphide Ni grade envelope
>0.2 % sulphide Ni grade envelope	>0.3 % sulphide Ni grade envelope


Downhole Data Legend

0 - 100	0 - 0.1	0 - 5
100 - 500	0.1 - 0.2	5 - 12
500 - 1000	0.2 - 0.3	12 - 20
1000 - 3600	0.3 - 0.5	20 - 25
	0.5 - 5	25 - 35

Pt+Pd (ppb) acNi (%) tdMg (%)

HoleID
 tdMg
 logged geology
 acNi
 Pt+Pd
 EOH

Note: Cross sections with no 0.1 % grade envelopes either do not contain enough information for interpretation, or the space between 0.2 % grade envelopes is all above 0.1 % sulphide Ni.



Legend

Dunite, serpentinitized dunite, and serpentinite	Green dunite and serpentinitized green dunite
Wehrilite and serpentinitized wehrilite	Olivine clinopyroxenite and clinopyroxenite
Hornblende clinopyroxenite, magnetite clinopyroxenite	Hornblende and feldspathic hornblende
Hornfels, calc-silicate, inclusion	Dikes of: diorite, granodiorite, hornblende, felspathic hornblende; undifferentiated
Phyllite	>0.1 % sulphide Ni grade envelope
>0.2 % sulphide Ni grade envelope	>0.3 % sulphide Ni grade envelope

Note: Cross sections with no 0.1 % grade envelopes either do not contain enough information for interpretation, or the space between 0.2 % grade envelopes is all above 0.1 % sulphide Ni.

Scale 1:2,000

0 25 50 metres


Downhole Data Legend


0 - 100	0.1 - 0.2	5 - 12
100 - 500	0.2 - 0.3	12 - 20
500 - 1000	0.3 - 0.5	20 - 25
1000 - 3600	0.5 - 5	25 - 35


Legend for Downhole Data:

- tdMg (%)
- acNi (%)
- Pt+Pd (ppb)

Vertical axis labels: HoleID, tdMg, logged geology, acNi, Pt+Pd, EOH







S

N

E 511300

6,481,200 mN 1,100 m

6,481,300 mN

6,481,400 mN

6,481,500 mN




6,481,600 mN

1,100 m

1,000 m


08-252

11



Appendix E

GENERAL SAMPLE PREPARATION METHODS



Comments

Receiving: Samples arrive via courier, post or by client drop-off; shipment inspected for completeness.

Sorting and Inspection: Samples sorted and inspected for quality of use (quantity and condition). Pulp samples inspected for homogeneity and fineness. Coarse pulps are screened or pulverized after getting client's approval.

Drying: Wet or damp samples are dried at 60°C (40°C if specified by the client).

Sieving: Soil and sediment sieved to -80 mesh ASTM (-177 microns) unless client specifies otherwise. Sieve cleaned by brush and compressed air between samples. Reference material G-1 (pulp made of granite blank) is carried as first sample in sequence (sieve>weigh>digest>analyse) to monitor background noise.


Crushing and Pulverizing: Rock and Drill Core crushed to 70% passing 10 mesh (2 mm), homogenized, riffle split (250 g subsample) and pulverized to 95% passing 150 mesh (100 microns). Crusher and pulverizer are cleaned by brush and compressed air between routine samples. Granite wash scours equipment after high-grade samples, between changes in rock colour and at end of each file. Granite is crushed and pulverized as first sample in sequence and carried through to analysis to monitor background noise.

Compositing: Equal weights of crushed, pulverized or sieved material from 2 or more samples are combined and pulverized for 60+ seconds to produce a homogeneous mixture.

Storage: Pulp samples (up to 100g for soils or sediments and up to 250 g for rock and drill core) are archived for 3 months at no cost. Soil and sediment rejects are discarded immediately. Rock and drill core rejects are stored for 3 months at no charge. Client may request additional storage, return or disposal of pulps and rejects after initial free storage period.

METHODS AND SPECIFICATIONS FOR ANALYTICAL PACKAGE GROUP 7TD – MULTI-ELEMENT ASSAY BY ICP-ES • 4-ACID DIGESTION

Analytical Process



Comments

Sample Preparation

All samples are dried at 60°C. Soil and sediment are sieved to -80 mesh (-177 µm). Moss-mats are disaggregated then sieved to yield -80 mesh sediment. Vegetation is pulverized or ashed (475°C). Rock and drill core is jaw crushed to 70% passing 10 mesh (2 mm), a 250 g riffle split is then pulverized to 95% passing 150 mesh (100 µm) in a mild-steel ring-and-puck mill. Pulp splits of 0.5 g are weighed into Teflon test tubes.

Sample Digestion

A 20 mL aliquot of the acid solution (2:2:1:1 H₂O-HF-HClO₄-HNO₃) is added, heated until fuming on a hot plate and taken to dryness. A 16 mL aliquot of 50% HCl is added to the residue and heated in a hot-water bath (~95°C) for 30 minutes. After cooling the solutions are transferred to 100 mL volumetric flasks and made to volume with 5% HCl.

Sample Analysis

Solutions aspirated into a Spectro Ciros Vision ICP emission spectrograph are analysed for a 22 element package comprising: Ag, Al, As, Bi, Ca, Cd, Co, Cr, Cu, Fe, K, Mg, Mn, Mo, Na, Ni, P, Pb, Sb, Sr, W and Zn. Very high grade samples may require a 1 g to 250 mL or 0.25 g to 250 mL sample to solution ratio for accurate determination.


Quality Control and Data Verification

An Analytical Batch (1 page) comprises 36 samples. QA/QC protocol incorporates a sample-prep blank (G-1) carried through all stages of preparation and analysis as the first sample, a pulp duplicate to monitor analytical precision, a -10 mesh rejects duplicate to monitor sub-sampling variation (drill core only), a reagent blank to measure background and an aliquot of in-house Standard Reference Materials like STD R3 to monitor accuracy.

Raw and final data undergo a final verification by a British Columbia Certified Assayer who signs the Analytical Report before it is released to the client.

METHODS AND SPECIFICATIONS FOR ANALYTICAL PACKAGE GROUP 8 – NI-SULPHIDE ASSAY BY ICP-ES

Analytical Process



Comments

Sample Preparation

Assaying is warranted for representative well-mineralized samples (eg. Ni > 0.5%). Rock and drill core is jaw crushed to 70% passing 10 mesh (2 mm), a 250 g aliquot is riffle split and pulverized to 95% passing 150 mesh (100 μ m) in a mild-steel ring-and-puck mill. Aliquots of 1.000 \pm 0.002 g are weighed into 250 mL plastic bottles. Acme's Quality Control protocol requires a pulp duplicates to monitor analytical precision and an aliquots of certified reference material UM-2 or UM-4 and/or in-house reference material R-3 to monitor accuracy in each batch of 36 samples. Drill core programs will include a pulp from a 2nd crushed fraction split (rejects duplicate) to measure method precision.

Sample Digestion

Samples are cold leached with a mixture of 40 mLs of 10% ammonium citrate and 20 mLs of 35% hydrogen peroxide that is agitated and allowed to leach. Solutions are filtered into a beaker and the residue is rinsed 3X with de-ionized water. HCl is added to the solution and is heated in hot water bath (95°C) for 1 hour then allowed to cool. Solutions are made up to volume (100 mL volumetric flask) with de-ionized water. Acme's QA/QC protocol requires simultaneous digestion of two reagent blanks inserted in each batch.

Sample Analysis

Sample solutions are aspirated into a Spectro Ciros Vision ICP emission spectrograph to determine Ni.

Calculation


This leach extracts Ni sulphide only.

Data Evaluation

Raw and final data from the ICP-ES undergoes a final verification by a British Columbia Certified Assayer who then signs the Analytical Report before it is released to the client.

METHODS AND SPECIFICATIONS FOR ANALYTICAL PACKAGE GROUP 3B & 3B-MS - PRECIOUS METALS BY FIRE GEOCHEM

Analytical Process



Comments

Sample Preparation

Soils and sediments are dried (60°C) and sieved to -80 mesh ASTM (-177 μm). Rocks and drill core are crushed and pulverized to 95% -150 mesh ASTM (-100 μm). Splits of 30 gm (client may select 50 gm option) are weighed into fire assay crucibles. Quality control samples comprising blanks, duplicates and reference materials OxF41 or FA-100S (Rocklabs CRM and in-house standard reference materials) added to each batch of 34 samples monitor background, precision and accuracy, respectively.

Sample Digestion

A fire assay charge comprising fluxes, litharge and a Ag inquant is custom mixed for each sample. Fusing at 1050°C for 1 hour liberates Au, Ag, Pt, Pd and Rh. The Pb button is recovered after cooling and cupelled at 950°C to render a Ag ± Au ± Pt ± Pd ± Rh dore bead. After weighing, the bead is parted in HNO₃ leaving Au (± PGE) sponge. Adding concentrated HCl dissolves the sponges.

Sample Analysis


Solutions are analysed by ICP-ES (Jarrel Ash AtomComp model 800 or 975) analysis of the solutions to determine Au, Pt, and Pd. Group 3B-MS analyses the same solutions by ICP-MS (Perkin Elmer Elan 6000) to determine Au, Pt, Pd and Rh to much lower detection limits. Owing to the limited solubility of Rh in a Ag inquant, results are qualitative.

Data Evaluation

Data is inspected by the Fire Assay Supervisor then undergoes final verification by a British Columbia Certified Assayer who signs the Analytical Report before release to the client.

METHODS AND SPECIFICATIONS FOR ANALYTICAL PACKAGE

GROUP 2A: TOTAL CARBON & SULPHUR



Comments

Sample Preparation

Soils and sediments are dried (60°C) and sieved to -80 mesh ASTM (-177 microns), rocks and drill core are crushed and pulverized to -150 mesh ASTM (-100 microns). Moss-mat samples are dried (60°C), macerated then sieved to recover -80 mesh sediment or ashed at 550°C (upon a client's request). Sample splits (0.1 g) are placed in Leco crucibles. Duplicate splits of crushed (rejects duplicate) and pulverized (pulp duplicate) fractions are included with every 36 drill core or trench samples to define sample homogeneity (reject duplicate) and analytical precision (pulp duplicate). Duplicate pulp splits (only) are included in every batch of soil, sediment and routine rock samples. A blank and in-house standard material STD CSC are carried through weighing, ignition and analytical stages to monitor accuracy.

Sample Analysis

Analysis is by infrared adsorption using a Leco CS244 or CS200 Carbon-Sulphur analyser. After precise weighing, induction flux is added and the sample is ignited at >1650°C in an induction furnace. A carrier gas sweeps up released carbon and sulphur to be measured by adsorption in an infrared spectrometric cell. Results are total and attributed to the presence of carbon and sulphur in all forms.

Data Evaluation

Raw and final data from the Leco Carbon-Sulphur analyser undergoes a final verification by a British Columbia Certified Assayer who must sign the analytical report before release to the client.

Hole 08-249



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Sandy Smeeton
 Receiving Lab: Canada-Smithers
 Received: June 20, 2008
 Report Date: September 16, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000559.3

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-249A
 P.O. Number
 Number of Samples: 46

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	43	Crush split and pulverize drill core to 200 mesh		
3B	43	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
7TD	46	4 Acid digestion ICP-ES analysis.	0.5	Completed
2A (Total S)	46	Analysis by Leco	0.1	Completed
8NiS	46	Leached with H2O2 + NH4 citrate	1	Completed
G8SG	2	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS

Version 3 : 3B data with correct standards included.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

ACME ANALYTICAL LABORATORIES LTD.

www.acmelab.com

Client:

Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
Vancouver BC V6E 3V7 Canada

Project:

Turnagain

Report Date:

September 16, 2008

Page:

2 of 3

Part 1

CERTIFICATE OF ANALYSIS

SMI08000559.3

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646101	Rock Pulp	0.02	I.S.	I.S.	I.S.	0.001	0.046	<0.02	<0.01	<2	0.401	0.027	0.12	12.85	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.16
646102	Drill Core	2.23	<2	13	14	<0.001	0.017	<0.02	<0.01	<2	0.098	0.012	0.13	8.62	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.30
646103	Drill Core	10.61	<2	48	48	<0.001	0.015	<0.02	<0.01	<2	0.124	0.014	0.15	9.35	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.08
646104	Drill Core	11.11	<2	42	53	<0.001	0.004	<0.02	<0.01	<2	0.125	0.014	0.15	9.06	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.86
646105	Drill Core	11.40	2	34	56	<0.001	0.002	<0.02	<0.01	<2	0.139	0.014	0.15	9.41	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.46
646106	Drill Core	12.13	2	15	20	<0.001	0.001	<0.02	<0.01	<2	0.152	0.014	0.16	9.90	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.27
646107	Drill Core	12.89	<2	12	15	<0.001	0.002	<0.02	<0.01	<2	0.160	0.014	0.15	9.54	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.80
646108	Drill Core	10.91	<2	10	18	<0.001	0.001	<0.02	<0.01	<2	0.171	0.014	0.14	9.16	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.20
646109	Drill Core	11.60	<2	13	14	<0.001	0.003	<0.02	<0.01	<2	0.166	0.013	0.15	9.20	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.48
646110	Drill Core	1.98	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	1.19	<0.02	0.08	<0.001	<0.01	<0.01	<0.01	2.02
646111	Drill Core	10.23	<2	8	10	<0.001	0.003	<0.02	<0.01	<2	0.148	0.013	0.15	9.34	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.29
646112	Drill Core	10.58	<2	14	21	<0.001	0.005	<0.02	<0.01	<2	0.124	0.013	0.14	9.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.78
646113	Drill Core	3.21	22	39	68	<0.001	0.009	<0.02	<0.01	<2	0.113	0.012	0.14	9.00	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.45
646114	Drill Core	7.23	9	311	355	<0.001	0.136	<0.02	<0.01	<2	0.319	0.018	0.14	9.69	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.09
646115	Drill Core	10.71	<2	21	27	<0.001	0.025	<0.02	<0.01	<2	0.096	0.010	0.14	8.02	<0.02	0.04	<0.001	<0.01	<0.01	0.01	3.75
646116	Drill Core	10.76	<2	<3	4	<0.001	0.005	<0.02	<0.01	<2	0.141	0.014	0.14	9.13	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.04
646117	Drill Core	11.02	<2	88	84	<0.001	0.034	<0.02	<0.01	<2	0.142	0.013	0.14	8.71	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.33
646118	Drill Core	5.35	6	84	68	<0.001	0.121	<0.02	<0.01	<2	0.177	0.017	0.12	9.36	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.44
646119	Drill Core	5.53	<2	7	8	<0.001	0.032	<0.02	<0.01	<2	0.071	0.009	0.10	5.46	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	10.77
646120	Drill Core	10.41	<2	7	12	<0.001	0.013	<0.02	<0.01	<2	0.077	0.013	0.13	8.48	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.50
646121	Drill Core	10.27	<2	5	11	<0.001	0.010	<0.02	<0.01	<2	0.082	0.015	0.14	9.20	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.10
646122	Drill Core	10.48	<2	<3	15	<0.001	0.014	<0.02	<0.01	2	0.095	0.016	0.14	9.35	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.24
646123	Drill Core	10.87	<2	7	13	<0.001	0.021	<0.02	<0.01	<2	0.097	0.014	0.14	9.24	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.57
646124	Drill Core	10.14	<2	9	19	<0.001	0.031	<0.02	<0.01	<2	0.110	0.014	0.14	9.24	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.15
646125	Rock Pulp	0.04	I.S.	I.S.	I.S.	<0.001	0.056	<0.02	0.02	<2	0.231	0.012	0.11	9.31	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	4.36
646126	Rock Pulp	0.04	I.S.	I.S.	I.S.	<0.001	0.031	<0.02	<0.01	<2	0.249	0.017	0.11	9.05	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.71
646127	Drill Core	10.30	<2	6	23	<0.001	0.017	<0.02	<0.01	<2	0.100	0.017	0.13	9.49	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.31
646128	Drill Core	10.47	<2	65	61	<0.001	0.026	<0.02	<0.01	<2	0.129	0.015	0.14	9.60	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.10
646129	Drill Core	5.89	<2	54	69	<0.001	0.031	<0.02	<0.01	<2	0.122	0.014	0.11	8.72	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.25
646130A	Drill Core	4.78	3	44	27	<0.001	0.038	<0.02	<0.01	<2	0.063	0.006	0.13	7.11	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	10.61



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 16, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000559.3

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD 2A	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG	
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	TOT/S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.02	0.001	0.001	0.001	0.01	0.01	0	
646101	Rock Pulp	<0.01	0.167	20.88	0.02	0.29	0.03	0.09	<0.01	2.74	3.91	0.046	0.394	0.025	1.17	1.77	N.A.
646102	Drill Core	0.01	0.077	20.54	0.07	0.91	0.23	0.09	<0.01	0.09	0.11	0.016	0.039	0.005	0.61	1.82	3.18
646103	Drill Core	<0.01	0.112	22.93	0.04	0.24	0.02	<0.01	<0.01	0.08	0.12	0.014	0.049	0.005	0.45	1.41	N.A.
646104	Drill Core	<0.01	0.087	23.10	0.08	0.45	0.02	<0.01	<0.01	0.04	0.07	0.004	0.050	0.005	0.45	1.49	N.A.
646105	Drill Core	<0.01	0.071	23.37	0.06	0.34	0.01	<0.01	<0.01	0.04	0.04	0.002	0.048	0.004	0.55	1.75	N.A.
646106	Drill Core	<0.01	0.108	24.14	0.03	0.13	0.01	<0.01	<0.01	0.05	0.06	0.002	0.049	0.004	0.49	1.60	N.A.
646107	Drill Core	<0.01	0.081	23.52	0.04	0.18	0.01	<0.01	<0.01	0.05	0.08	0.003	0.060	0.005	0.50	1.67	N.A.
646108	Drill Core	<0.01	0.142	23.52	0.04	0.20	<0.01	<0.01	<0.01	0.05	0.08	0.002	0.083	0.006	0.35	1.36	N.A.
646109	Drill Core	<0.01	0.146	24.03	0.05	0.30	<0.01	<0.01	<0.01	0.07	0.08	0.002	0.078	0.006	0.32	1.21	N.A.
646110	Drill Core	0.02	0.002	0.25	0.07	7.94	3.71	1.12	<0.01	<0.01	<0.02	<0.001	<0.001	<0.001	0.07	0.04	N.A.
646111	Drill Core	<0.01	0.173	22.82	0.06	0.38	<0.01	<0.01	<0.01	0.07	0.10	0.003	0.090	0.007	0.32	1.53	N.A.
646112	Drill Core	0.01	0.111	21.88	0.13	0.81	<0.01	<0.01	<0.01	0.08	0.11	0.005	0.094	0.008	0.23	1.22	N.A.
646113	Drill Core	0.02	0.157	20.95	0.15	0.92	0.03	0.04	<0.01	0.10	0.10	0.009	0.089	0.008	0.23	1.02	N.A.
646114	Drill Core	<0.01	0.119	23.19	0.03	0.16	<0.01	<0.01	<0.01	0.62	0.63	0.138	0.340	0.017	0.70	1.46	N.A.
646115	Drill Core	0.06	0.065	17.89	0.15	2.31	0.03	0.32	<0.01	0.10	0.10	0.025	0.092	0.008	0.23	0.96	N.A.
646116	Drill Core	<0.01	0.103	24.09	0.02	0.08	<0.01	<0.01	<0.01	0.10	0.08	0.005	0.135	0.011	0.20	1.75	N.A.
646117	Drill Core	<0.01	0.151	22.76	0.03	0.45	<0.01	<0.01	<0.01	0.18	0.14	0.033	0.135	0.011	0.26	1.35	N.A.
646118	Drill Core	<0.01	0.416	21.24	0.04	0.24	<0.01	<0.01	<0.01	0.60	0.67	0.116	0.180	0.016	0.60	2.32	N.A.
646119	Drill Core	0.01	0.197	13.70	0.14	0.74	0.08	<0.01	<0.01	0.30	0.39	0.030	0.069	0.007	0.27	0.69	N.A.
646120	Drill Core	<0.01	0.113	22.38	0.04	0.27	<0.01	<0.01	<0.01	0.21	0.21	0.013	0.074	0.012	0.21	1.24	N.A.
646121	Drill Core	<0.01	0.103	23.06	0.02	0.13	<0.01	<0.01	<0.01	0.21	0.22	0.010	0.080	0.013	0.25	2.10	N.A.
646122	Drill Core	<0.01	0.120	22.86	0.03	0.18	<0.01	<0.01	<0.01	0.21	0.23	0.013	0.091	0.014	0.22	1.57	N.A.
646123	Drill Core	0.01	0.111	22.90	0.06	0.35	<0.01	<0.01	<0.01	0.23	0.25	0.020	0.095	0.012	0.27	1.60	N.A.
646124	Drill Core	0.02	0.094	23.49	0.06	0.29	<0.01	<0.01	<0.01	0.30	0.32	0.030	0.107	0.012	0.30	1.55	N.A.
646125	Rock Pulp	0.02	1.106	13.69	0.19	4.20	0.32	0.11	<0.01	0.41	0.44	0.054	0.186	0.007	0.37	0.37	N.A.
646126	Rock Pulp	0.01	0.130	23.79	0.02	0.31	<0.01	0.07	<0.01	1.04	1.30	0.028	0.215	0.012	0.82	2.33	N.A.
646127	Drill Core	0.03	0.142	22.03	0.18	0.65	<0.01	<0.01	<0.01	0.38	0.37	0.014	0.096	0.015	0.28	1.35	N.A.
646128	Drill Core	0.02	0.127	23.27	0.02	0.11	<0.01	<0.01	<0.01	0.52	0.62	0.024	0.129	0.013	0.30	1.12	N.A.
646129	Drill Core	<0.01	0.062	21.21	0.03	0.35	<0.01	<0.01	<0.01	0.58	0.70	0.023	0.125	0.013	0.30	1.21	N.A.
646130A	Drill Core	0.07	0.074	12.98	0.28	3.14	<0.01	<0.01	<0.01	0.24	0.36	0.027	0.061	0.005	0.20	0.74	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 16, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000559.3

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646130B	Drill Core	<0.01	<2	35	28	<0.001	0.038	<0.02	<0.01	<2	0.063	0.006	0.13	7.12	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	10.71
646131	Drill Core	10.97	5	392	243	<0.001	0.117	<0.02	<0.01	<2	0.211	0.020	0.12	12.33	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.62
646132	Drill Core	12.32	4	284	226	0.010	0.346	<0.02	<0.01	<2	0.490	0.045	0.11	19.34	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	2.49
646133	Drill Core	11.55	<2	95	81	<0.001	0.105	<0.02	<0.01	<2	0.229	0.022	0.11	12.05	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.74
646134	Drill Core	7.70	<2	10	27	<0.001	0.029	<0.02	<0.01	<2	0.115	0.016	0.12	8.99	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.46
646135	Drill Core	2.94	3	11	16	<0.001	0.017	<0.02	<0.01	<2	0.058	0.008	0.11	6.14	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	7.29
646136	Drill Core	7.50	<2	<3	10	<0.001	0.013	<0.02	<0.01	<2	0.056	0.007	0.08	5.39	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	8.02
646137	Drill Core	2.57	<2	<3	10	<0.001	0.011	<0.02	<0.01	<2	0.143	0.015	0.12	8.53	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.15
646138	Drill Core	11.02	<2	14	14	<0.001	0.017	<0.02	<0.01	<2	0.130	0.016	0.13	9.02	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.17
646139	Drill Core	10.64	<2	9	33	<0.001	0.031	<0.02	<0.01	<2	0.179	0.023	0.13	10.79	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.92
646140	Drill Core	1.73	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.06	1.03	<0.02	0.08	<0.001	<0.01	<0.01	<0.01	1.85
646141	Drill Core	10.74	<2	28	24	<0.001	0.023	<0.02	<0.01	<2	0.151	0.016	0.13	9.71	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.14
646142	Drill Core	10.47	<2	9	24	<0.001	0.023	<0.02	<0.01	<2	0.143	0.014	0.14	9.47	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.23
646143	Drill Core	11.24	<2	40	45	<0.001	0.041	<0.02	<0.01	<2	0.181	0.019	0.14	10.03	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.73
646144	Drill Core	10.06	5	93	37	<0.001	0.031	<0.02	<0.01	<2	0.137	0.015	0.13	11.06	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	2.05
646145	Drill Core	11.02	<2	8	24	<0.001	0.034	<0.02	<0.01	<2	0.124	0.011	0.15	10.08	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.52



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 16, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000559.3

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD 2A Leco	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG	
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	TOT/S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.02	0.001	0.001	0.001	0.01	0.01	0	
646130B	Drill Core	0.07	0.070	12.91	0.29	3.25	<0.01	<0.01	<0.01	0.23	0.35	0.029	0.061	0.005	0.25	0.95	N.A.
646131	Drill Core	0.01	0.056	19.76	0.04	0.34	<0.01	<0.01	<0.01	1.64	2.22	0.095	0.206	0.019	0.69	1.36	N.A.
646132	Drill Core	<0.01	0.056	16.39	0.02	0.09	<0.01	<0.01	<0.01	5.08	6.92	0.316	0.462	0.045	1.90	1.06	2.80
646133	Drill Core	<0.01	0.060	21.63	0.01	0.06	<0.01	<0.01	<0.01	2.09	2.66	0.112	0.227	0.020	0.81	1.73	N.A.
646134	Drill Core	<0.01	0.075	22.53	0.01	0.06	<0.01	<0.01	<0.01	0.81	0.91	0.029	0.109	0.014	0.46	1.89	N.A.
646135	Drill Core	<0.01	0.176	17.09	0.06	0.33	0.05	<0.01	<0.01	0.44	0.45	0.015	0.047	0.006	0.20	1.06	N.A.
646136	Drill Core	<0.01	0.211	15.52	0.08	0.41	0.05	<0.01	<0.01	0.35	0.31	0.011	0.050	0.006	0.18	1.13	N.A.
646137	Drill Core	<0.01	0.175	22.78	0.02	0.08	<0.01	<0.01	<0.01	0.30	0.32	0.010	0.146	0.013	0.30	1.76	N.A.
646138	Drill Core	<0.01	0.185	23.70	0.02	0.08	<0.01	<0.01	<0.01	0.40	0.43	0.016	0.127	0.014	0.28	1.97	N.A.
646139	Drill Core	<0.01	0.146	20.05	0.03	0.37	<0.01	<0.01	<0.01	0.95	1.12	0.032	0.198	0.022	0.58	1.88	N.A.
646140	Drill Core	0.01	<0.001	0.19	0.06	7.15	3.48	1.09	<0.01	<0.01	<0.02	<0.001	<0.001	<0.001	0.05	0.04	N.A.
646141	Drill Core	0.02	0.116	21.50	0.08	0.77	<0.01	0.04	<0.01	0.70	0.79	0.022	0.154	0.014	0.30	1.10	N.A.
646142	Drill Core	<0.01	0.173	22.72	0.02	0.13	<0.01	<0.01	<0.01	0.65	0.73	0.023	0.145	0.013	0.36	1.65	N.A.
646143	Drill Core	<0.01	0.187	20.10	0.04	0.23	0.01	<0.01	<0.01	1.26	1.53	0.047	0.207	0.019	0.50	1.29	N.A.
646144	Drill Core	0.02	0.145	19.69	0.10	0.87	<0.01	<0.01	<0.01	0.73	0.84	0.024	0.133	0.013	0.30	1.30	N.A.
646145	Drill Core	<0.01	0.168	21.83	0.05	0.37	<0.01	<0.01	<0.01	0.88	0.41	0.023	0.111	0.009	0.30	1.52	N.A.

QUALITY CONTROL REPORT

SMI08000559.3

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca
Unit	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01
646137	Drill Core	2.57	<2	<3	10	<0.001	0.011	<0.02	<0.01	<2	0.143	0.015	0.12	8.53	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
Pulp Duplicates																				
646101	Rock Pulp	0.02	I.S.	I.S.	I.S.	0.001	0.046	<0.02	<0.01	<2	0.401	0.027	0.12	12.85	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646101	QC																			
646121	Drill Core	10.27	<2	5	11	<0.001	0.010	<0.02	<0.01	<2	0.082	0.015	0.14	9.20	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646121	QC																			
646127	Drill Core	10.30	<2	6	23	<0.001	0.017	<0.02	<0.01	<2	0.100	0.017	0.13	9.49	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646127	QC					<0.001	0.017	<0.02	<0.01	<2	0.099	0.016	0.13	9.43	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646130B	Drill Core	<0.01	<2	35	28	<0.001	0.038	<0.02	<0.01	<2	0.063	0.006	0.13	7.12	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
REP 646130B	QC																			
646133	Drill Core	11.55	<2	95	81	<0.001	0.105	<0.02	<0.01	<2	0.229	0.022	0.11	12.05	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646133	QC		<2	83	84															
646136	Drill Core	7.50	<2	<3	10	<0.001	0.013	<0.02	<0.01	<2	0.056	0.007	0.08	5.39	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646136	QC																			
646139	Drill Core	10.64	<2	9	33	<0.001	0.031	<0.02	<0.01	<2	0.179	0.023	0.13	10.79	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646139	QC					<0.001	0.032	<0.02	<0.01	<2	0.181	0.023	0.13	10.82	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646145	Drill Core	11.02	<2	8	24	<0.001	0.034	<0.02	<0.01	<2	0.124	0.011	0.15	10.08	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646145	QC																			
Core Reject Duplicates																				
646117	Drill Core	11.02	<2	88	84	<0.001	0.034	<0.02	<0.01	<2	0.142	0.013	0.14	8.71	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
DUP 646117	QC		<2	94	85	<0.001	0.034	<0.02	<0.01	<2	0.142	0.013	0.14	8.79	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
Reference Materials																				
STD CDN-PGMS-14	Standard		235	92	404															
STD CDN-PGMS-14	Standard		229	101	408															
STD CSC	Standard																			
STD CSC	Standard																			
STD CSC	Standard																			
STD CSC	Standard																			
STD FA10R	Standard		454	439	430															

QUALITY CONTROL REPORT

SMI08000559.3

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD 2A	Leco	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	TOT/S		Cu	Ni	Co	Fe	Mg	SG
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.02	0.001	0.001	0.001	0.01	0.01	0
646137	Drill Core	<0.01	0.175	22.78	0.02	0.08	<0.01	<0.01	<0.01	0.30	0.32	0.010	0.146	0.013	0.30	1.76	N.A.
Pulp Duplicates																	
646101	Rock Pulp	<0.01	0.167	20.88	0.02	0.29	0.03	0.09	<0.01	2.74	3.91	0.046	0.394	0.025	1.17	1.77	N.A.
REP 646101	QC											0.046	0.391	0.025	1.18	1.78	
646121	Drill Core	<0.01	0.103	23.06	0.02	0.13	<0.01	<0.01	<0.01	0.21	0.22	0.010	0.080	0.013	0.25	2.10	N.A.
REP 646121	QC										0.22						
646127	Drill Core	0.03	0.142	22.03	0.18	0.65	<0.01	<0.01	<0.01	0.38	0.37	0.014	0.096	0.015	0.28	1.35	N.A.
REP 646127	QC	0.03	0.138	21.67	0.17	0.64	<0.01	<0.01	<0.01	0.37							
646130B	Drill Core	0.07	0.070	12.91	0.29	3.25	<0.01	<0.01	<0.01	0.23	0.35	0.029	0.061	0.005	0.25	0.95	N.A.
REP 646130B	QC											0.030	0.061	0.005	0.30	1.13	
646133	Drill Core	<0.01	0.060	21.63	0.01	0.06	<0.01	<0.01	<0.01	2.09	2.66	0.112	0.227	0.020	0.81	1.73	N.A.
REP 646133	QC																
646136	Drill Core	<0.01	0.211	15.52	0.08	0.41	0.05	<0.01	<0.01	0.35	0.31	0.011	0.050	0.006	0.18	1.13	N.A.
REP 646136	QC											0.011	0.051	0.006	0.19	1.17	
646139	Drill Core	<0.01	0.146	20.05	0.03	0.37	<0.01	<0.01	<0.01	0.95	1.12	0.032	0.198	0.022	0.58	1.88	N.A.
REP 646139	QC	<0.01	0.145	20.04	0.03	0.38	<0.01	<0.01	<0.01	0.97							
646145	Drill Core	<0.01	0.168	21.83	0.05	0.37	<0.01	<0.01	<0.01	0.88	0.41	0.023	0.111	0.009	0.30	1.52	N.A.
REP 646145	QC										0.42						
Core Reject Duplicates																	
646117	Drill Core	<0.01	0.151	22.76	0.03	0.45	<0.01	<0.01	<0.01	0.18	0.14	0.033	0.135	0.011	0.26	1.35	N.A.
DUP 646117	QC	0.02	0.153	22.78	0.03	0.46	<0.01	<0.01	<0.01	0.18	0.16	0.034	0.135	0.011	0.27	1.53	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard										4.00						
STD CSC	Standard										4.27						
STD CSC	Standard										4.23						
STD CSC	Standard										4.35						
STD FA10R	Standard																

QUALITY CONTROL REPORT

SMI08000559.3

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD 2A Leco	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		P	Cr	Mg	Ti	Al	Na	K	W	S TOT/S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
STD FA10R	Standard															
STD OREAS76A	Standard									<0.02						
STD OREAS76A	Standard									17.86						
STD OREAS76A	Standard									17.28						
STD OREAS76A	Standard									17.13						
STD R3NI	Standard										0.709	0.413	0.054	5.05	0.14	
STD R3NI	Standard										0.782	0.407	0.047	4.95	0.14	
STD R3T	Standard	0.05	0.020	1.66	0.18	2.45	0.31	0.59	<0.01	15.32						
STD R3T	Standard	0.05	0.021	1.67	0.18	2.46	0.31	0.60	<0.01	15.58						
STD R3T	Standard	0.05	0.020	1.66	0.17	2.44	0.32	0.59	<0.01	15.96						
STD R3T	Standard	0.05	0.020	1.67	0.19	2.47	0.32	0.59	0.01	16.00						
STD R3T Expected		0.05	0.02	1.64		2.44	0.31	0.59								
STD R3NI Expected												0.42				
STD FA10R Expected																
STD CDN-PGMS-14																
STD CSC Expected										4.19						
STD OREAS76A Expected										18						
BLK	Blank									<0.02						
BLK	Blank									<0.02						
BLK	Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank									<0.02						
BLK	Blank															
BLK	Blank															
BLK	Blank															
BLK	Blank															
BLK	Blank															
BLK	Blank									<0.02						

QUALITY CONTROL REPORT

SMI08000559.3

		WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca
		kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2	0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.40	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.32
G1	Prep Blank	<0.01	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.44	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.45

QUALITY CONTROL REPORT

SMI08000559.3

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD 2A Leco	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG	
		P	Cr	Mg	Ti	Al	Na	K	W	S TOT/S	Cu	Ni	Co	Fe	Mg	SG	
		%	%	%	%	%	%	%	%	%	%	%	%	%	%		
Prep Wash		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.02	0.001	0.001	0.001	0.01	0.01	0
G1	Prep Blank	0.08	<0.001	0.62	0.22	7.84	2.60	3.01	<0.01	<0.01	<0.02	<0.001	<0.001	<0.001	0.11	0.04	N.A.
G1	Prep Blank	0.07	0.001	0.65	0.24	8.06	2.75	3.09	<0.01	<0.01	<0.02	<0.001	<0.001	<0.001	0.10	0.03	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Sandy Smeeton
 Receiving Lab: Canada-Smithers
 Received: June 26, 2008
 Report Date: August 27, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000569.1

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-249B
 P.O. Number
 Number of Samples: 51

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	47	Crush split and pulverize drill core to 200 mesh		
3B	51	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
7TD	51	4 Acid digestion ICP-ES analysis.	0.5	Completed
8NiS	51	Leached with H2O2 + NH4 citrate	1	Completed
2A (TOTAL S)	51	Analysis by Leco	0.1	Completed
G8SG	3	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS

Include 3B data with correct standards.



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

ACME ANALYTICAL LABORATORIES LTD.

www.acmelab.com

Client:

Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project:

Turnagain

Report Date:

August 27, 2008

Page:

2 of 3

Part 1

CERTIFICATE OF ANALYSIS

SMI08000569.1

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646146	Drill Core	11.25	<2	15	37	<0.001	0.046	<0.02	<0.01	<2	0.143	0.015	0.16	10.88	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.44
646147	Drill Core	12.48	<2	33	38	<0.001	0.089	<0.02	<0.01	<2	0.091	0.014	0.11	10.59	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	7.23
646148	Drill Core	4.72	<2	16	51	<0.001	0.062	<0.02	<0.01	<2	0.142	0.017	0.10	9.13	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	7.06
646149	Drill Core	3.67	<2	3	20	<0.001	0.030	<0.02	<0.01	<2	0.039	0.009	0.19	10.80	<0.02	<0.01	<0.001	<0.01	<0.01	0.05	12.61
646150	Rock Pulp	0.02	I.S.	I.S.	I.S.	0.001	0.044	<0.02	<0.01	<2	0.381	0.026	0.11	12.48	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.08
646151	Rock Pulp	0.03	I.S.	I.S.	I.S.	0.002	0.012	<0.02	<0.01	<2	0.084	0.003	0.08	4.61	<0.02	0.02	<0.001	<0.01	<0.01	<0.01	3.54
646152	Drill Core	3.89	<2	15	25	<0.001	0.040	<0.02	<0.01	<2	0.099	0.011	0.10	10.11	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	1.51
646153	Drill Core	11.76	<2	40	33	<0.001	0.044	<0.02	<0.01	<2	0.142	0.017	0.11	9.84	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	1.78
646154	Drill Core	12.81	<2	20	37	<0.001	0.045	<0.02	<0.01	<2	0.158	0.018	0.12	10.76	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.45
646155	Drill Core	11.70	<2	45	84	<0.001	0.117	<0.02	<0.01	<2	0.206	0.025	0.11	13.46	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.24
646156	Drill Core	12.18	3	54	114	<0.001	0.091	<0.02	<0.01	<2	0.110	0.015	0.09	10.31	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	5.21
646157	Drill Core	5.27	3	213	135	<0.001	0.387	<0.02	<0.01	<2	0.287	0.034	0.15	19.96	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	4.31
646158	Drill Core	5.34	<2	249	161	<0.001	0.052	<0.02	<0.01	<2	0.088	0.010	0.11	9.41	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.04
646159	Drill Core	5.81	<2	70	121	<0.001	0.058	<0.02	<0.01	<2	0.125	0.017	0.11	11.35	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	3.26
646160A	Drill Core	5.16	<2	55	63	<0.001	0.090	<0.02	<0.01	<2	0.157	0.020	0.13	13.63	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.85
646160B	Drill Core	<0.01	<2	122	59	<0.001	0.087	<0.02	<0.01	<2	0.157	0.020	0.13	13.18	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.80
646161	Drill Core	10.93	<2	39	35	<0.001	0.089	<0.02	<0.01	<2	0.112	0.015	0.10	10.07	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.61
646162	Drill Core	11.03	<2	97	90	<0.001	0.091	<0.02	<0.01	<2	0.228	0.023	0.12	12.13	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.06
646163	Drill Core	11.85	13	142	129	<0.001	0.273	<0.02	<0.01	<2	0.420	0.020	0.13	10.32	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.23
646164	Drill Core	10.69	7	113	190	<0.001	0.276	<0.02	<0.01	3	0.534	0.028	0.15	11.99	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.94
646165	Drill Core	10.57	3	168	130	<0.001	0.390	<0.02	<0.01	2	0.505	0.031	0.12	11.89	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.91
646166	Drill Core	11.17	<2	140	168	<0.001	0.156	<0.02	<0.01	<2	0.353	0.028	0.13	11.72	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.74
646167	Drill Core	11.32	4	90	107	<0.001	0.129	<0.02	<0.01	<2	0.258	0.026	0.11	10.90	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.02
646168	Drill Core	10.17	9	245	237	<0.001	0.152	<0.02	<0.01	<2	0.205	0.020	0.13	10.88	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.03
646169	Drill Core	11.24	5	116	193	<0.001	0.154	<0.02	<0.01	<2	0.278	0.024	0.12	10.82	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.02
646170	Drill Core	10.76	3	34	169	<0.001	0.015	<0.02	<0.01	2	0.109	0.014	0.14	9.41	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.08
646171	Drill Core	10.87	<2	52	48	<0.001	0.012	<0.02	<0.01	<2	0.096	0.013	0.13	8.31	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.07
646172	Drill Core	11.37	6	53	58	<0.001	0.180	<0.02	<0.01	4	0.334	0.019	0.12	10.53	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.74
646173	Drill Core	11.56	3	42	44	<0.001	0.127	<0.02	<0.01	2	0.316	0.024	0.13	11.31	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.53
646174	Drill Core	10.91	<2	23	19	<0.001	0.005	<0.02	<0.01	3	0.074	0.009	0.11	6.43	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	6.97



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

ACME ANALYTICAL LABORATORIES LTD.

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: August 27, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000569.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0	
646146	Drill Core	<0.01	0.124	22.94	0.07	0.46	<0.01	<0.01	<0.01	1.16	0.036	0.131	0.015	0.57	1.60	1.44	N.A.
646147	Drill Core	<0.01	0.143	14.61	0.09	0.41	0.04	<0.01	<0.01	1.91	0.081	0.076	0.013	0.57	0.77	2.93	N.A.
646148	Drill Core	<0.01	0.184	15.25	0.10	0.48	0.05	0.43	<0.01	1.81	0.057	0.140	0.017	0.51	0.72	2.33	N.A.
646149	Drill Core	0.03	0.020	7.24	0.91	4.86	0.03	<0.01	<0.01	0.45	0.030	0.035	0.005	0.32	0.36	0.52	N.A.
646150	Rock Pulp	<0.01	0.193	20.45	0.02	0.26	0.03	0.10	<0.01	3.11	0.046	0.381	0.024	1.15	1.68	4.15	N.A.
646151	Rock Pulp	0.05	0.078	1.58	0.30	7.59	2.33	1.03	<0.01	0.30	0.008	0.010	<0.001	0.47	0.13	0.26	N.A.
646152	Drill Core	<0.01	0.099	19.76	0.05	0.46	0.01	<0.01	<0.01	1.06	0.035	0.101	0.011	0.32	0.98	1.29	N.A.
646153	Drill Core	<0.01	0.122	19.50	0.05	0.26	0.01	0.29	<0.01	1.46	0.040	0.143	0.018	0.46	1.10	1.82	N.A.
646154	Drill Core	<0.01	0.132	20.30	0.03	0.21	<0.01	0.11	<0.01	1.61	0.045	0.172	0.019	1.00	2.37	2.06	N.A.
646155	Drill Core	<0.01	0.093	18.14	0.03	0.18	0.01	0.02	<0.01	3.49	0.109	0.198	0.027	0.81	0.88	4.42	N.A.
646156	Drill Core	<0.01	0.115	16.15	0.06	0.37	0.03	0.04	<0.01	2.47	0.077	0.101	0.015	0.64	1.05	3.06	N.A.
646157	Drill Core	<0.01	0.082	12.85	0.05	0.57	0.05	0.33	<0.01	6.53	0.363	0.246	0.035	1.77	0.76	9.01	N.A.
646158	Drill Core	<0.01	0.019	21.44	0.01	0.09	<0.01	0.26	<0.01	1.76	0.051	0.089	0.010	0.97	1.97	2.21	N.A.
646159	Drill Core	<0.01	0.077	17.62	0.04	0.16	0.02	0.36	<0.01	2.13	0.063	0.132	0.018	0.84	1.73	2.69	N.A.
646160A	Drill Core	<0.01	0.057	19.23	0.02	0.12	<0.01	0.35	<0.01	2.62	0.082	0.155	0.021	0.68	1.13	3.28	N.A.
646160B	Drill Core	<0.01	0.053	18.97	0.02	0.12	<0.01	0.10	<0.01	2.59	0.076	0.153	0.021	0.60	0.98	3.38	N.A.
646161	Drill Core	<0.01	0.066	20.11	0.04	0.16	<0.01	<0.01	<0.01	1.69	0.084	0.114	0.016	0.72	1.60	2.18	N.A.
646162	Drill Core	<0.01	0.152	22.06	0.01	0.11	<0.01	<0.01	<0.01	1.59	0.092	0.229	0.025	0.70	1.41	2.13	2.94
646163	Drill Core	<0.01	0.331	21.69	0.04	0.41	<0.01	0.03	<0.01	1.76	0.268	0.410	0.021	1.17	1.53	2.19	N.A.
646164	Drill Core	<0.01	0.235	18.50	0.05	0.94	<0.01	0.01	<0.01	1.90	0.246	0.514	0.030	1.21	1.71	2.35	N.A.
646165	Drill Core	0.01	0.156	19.01	0.07	0.58	<0.01	<0.01	<0.01	2.23	0.390	0.533	0.036	1.29	1.46	2.67	N.A.
646166	Drill Core	0.01	0.158	19.40	0.07	0.81	<0.01	0.24	<0.01	2.19	0.159	0.380	0.033	0.99	1.14	2.74	N.A.
646167	Drill Core	<0.01	0.166	22.52	0.01	0.07	<0.01	0.17	<0.01	1.82	0.137	0.268	0.028	0.93	1.57	2.33	N.A.
646168	Drill Core	<0.01	0.168	22.73	0.02	0.14	<0.01	<0.01	<0.01	1.18	0.154	0.204	0.021	0.77	1.56	1.42	N.A.
646169	Drill Core	<0.01	0.199	23.05	0.02	0.09	<0.01	0.29	<0.01	1.15	0.153	0.274	0.024	0.82	1.48	1.41	N.A.
646170	Drill Core	<0.01	0.167	23.80	0.02	0.12	<0.01	0.15	<0.01	0.23	0.016	0.115	0.013	0.27	1.73	0.27	N.A.
646171	Drill Core	<0.01	0.283	23.13	0.03	0.15	<0.01	0.03	<0.01	0.19	0.012	0.094	0.011	0.23	1.33	0.19	N.A.
646172	Drill Core	<0.01	0.196	21.33	0.06	0.36	<0.01	0.02	<0.01	1.26	0.187	0.352	0.021	1.06	1.83	1.53	2.91
646173	Drill Core	<0.01	0.099	18.44	0.09	0.42	0.01	0.19	<0.01	1.35	0.126	0.308	0.027	0.84	1.22	1.71	N.A.
646174	Drill Core	<0.01	0.167	16.69	0.09	0.46	0.04	0.08	<0.01	0.06	0.005	0.059	0.006	0.17	0.76	0.09	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: August 27, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000569.1

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646175	Rock Pulp	0.03	I.S.	I.S.	I.S.	0.001	0.012	<0.02	<0.01	<2	0.085	0.003	0.07	4.67	<0.02	0.02	<0.001	<0.01	<0.01	<0.01	3.70
646176	Rock Pulp	0.01	I.S.	I.S.	I.S.	<0.001	0.028	<0.02	<0.01	<2	0.248	0.016	0.11	8.85	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.69
646177	Drill Core	11.34	<2	8	3	<0.001	0.008	<0.02	<0.01	3	0.044	0.006	0.10	4.68	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	11.42
646178	Drill Core	6.34	<2	18	16	<0.001	0.004	<0.02	<0.01	3	0.103	0.011	0.13	8.48	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.51
646179	Drill Core	4.93	60	318	324	<0.001	0.471	<0.02	<0.01	8	0.514	0.017	0.15	10.80	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.92
646180	Drill Core	1.66	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.06	1.00	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	1.78
646181	Drill Core	11.26	9	161	226	<0.001	0.038	<0.02	<0.01	3	0.171	0.013	0.14	9.39	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.82
646182	Drill Core	12.13	26	26	25	<0.001	0.226	<0.02	<0.01	2	0.322	0.017	0.13	9.45	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.47
646183	Drill Core	4.18	3	7	6	<0.001	0.066	<0.02	<0.01	<2	0.240	0.015	0.12	8.35	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	5.77
646184	Drill Core	6.20	<2	15	12	<0.001	0.031	<0.02	<0.01	<2	0.036	0.008	0.11	5.77	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	14.30
646185	Drill Core	11.64	<2	5	4	<0.001	0.033	<0.02	<0.01	<2	0.033	0.009	0.10	5.48	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	13.34
646186	Drill Core	11.81	<2	20	25	<0.001	0.047	<0.02	<0.01	<2	0.081	0.015	0.11	7.51	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	9.84
646187	Drill Core	11.41	<2	26	30	<0.001	0.049	<0.02	<0.01	<2	0.125	0.017	0.11	9.15	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	9.12
646188	Drill Core	11.24	<2	9	14	<0.001	0.032	<0.02	<0.01	<2	0.079	0.015	0.12	7.95	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	8.21
646189	Drill Core	11.86	<2	25	16	<0.001	0.029	<0.02	<0.01	<2	0.121	0.018	0.14	9.95	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.92
646190A	Drill Core	11.44	<2	12	42	<0.001	0.050	<0.02	0.01	<2	0.141	0.018	0.17	9.73	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	3.10
646190B	Drill Core	<0.01	<2	25	21	<0.001	0.049	<0.02	0.01	<2	0.160	0.020	0.16	10.46	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.04
646191	Drill Core	11.01	<2	9	8	<0.001	0.019	<0.02	<0.01	<2	0.087	0.013	0.14	9.10	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	4.05
646192	Drill Core	10.31	<2	16	10	<0.001	0.018	<0.02	<0.01	<2	0.112	0.014	0.13	8.68	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.35
646193	Drill Core	10.02	<2	12	6	<0.001	0.019	<0.02	<0.01	<2	0.115	0.014	0.14	9.19	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.94
646194	Drill Core	10.75	<2	8	6	<0.001	0.018	<0.02	<0.01	<2	0.098	0.013	0.14	8.80	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.67



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: August 27, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000569.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0	
646175	Rock Pulp	0.05	0.077	1.61	0.31	8.31	2.31	1.23	<0.01	0.26	0.008	0.011	<0.001	0.53	0.13	0.27	N.A.
646176	Rock Pulp	<0.01	0.151	23.65	0.02	0.29	<0.01	0.26	<0.01	1.05	0.030	0.218	0.013	0.82	2.31	1.37	N.A.
646177	Drill Core	<0.01	0.175	12.75	0.14	0.75	0.06	0.28	<0.01	0.08	0.008	0.036	0.004	0.14	0.41	0.13	N.A.
646178	Drill Core	<0.01	0.295	20.74	0.06	0.26	0.02	0.05	<0.01	0.07	0.004	0.086	0.008	0.18	0.85	0.10	N.A.
646179	Drill Core	<0.01	0.103	22.86	0.02	0.09	<0.01	0.07	<0.01	0.78	0.490	0.489	0.014	1.25	1.14	0.97	N.A.
646180	Drill Core	<0.01	0.002	0.21	0.06	6.87	3.28	1.12	<0.01	<0.01	<0.001	<0.001	<0.001	0.05	0.03	0.03	N.A.
646181	Drill Core	<0.01	0.224	22.59	0.04	0.27	0.01	0.05	<0.01	0.17	0.044	0.135	0.009	0.35	1.08	0.19	N.A.
646182	Drill Core	0.01	0.237	20.01	0.05	0.27	0.03	<0.01	<0.01	0.66	0.237	0.312	0.014	0.84	1.16	0.77	N.A.
646183	Drill Core	<0.01	0.179	16.57	0.08	0.72	0.04	<0.01	<0.01	0.68	0.065	0.241	0.013	0.46	0.70	0.83	N.A.
646184	Drill Core	0.05	0.164	9.95	0.25	0.96	0.08	<0.01	<0.01	0.35	0.033	0.032	0.006	0.25	0.24	0.58	N.A.
646185	Drill Core	0.02	0.196	10.88	0.18	1.24	0.09	<0.01	<0.01	0.52	0.037	0.029	0.007	0.32	0.28	0.81	N.A.
646186	Drill Core	0.01	0.207	13.69	0.10	0.71	0.08	0.02	<0.01	1.04	0.050	0.076	0.014	0.40	0.46	1.48	N.A.
646187	Drill Core	0.01	0.201	14.36	0.11	0.67	0.06	<0.01	<0.01	1.32	0.048	0.113	0.015	0.46	0.54	1.85	N.A.
646188	Drill Core	<0.01	0.191	15.85	0.09	0.49	0.06	<0.01	<0.01	0.85	0.035	0.076	0.013	0.72	1.67	1.12	N.A.
646189	Drill Core	<0.01	0.153	20.82	0.05	0.26	0.01	<0.01	<0.01	0.84	0.028	0.106	0.014	0.39	1.06	1.04	N.A.
646190A	Drill Core	<0.01	0.705	19.54	0.09	0.78	0.01	<0.01	<0.01	1.02	0.044	0.130	0.016	0.38	1.07	1.40	N.A.
646190B	Drill Core	<0.01	0.447	19.14	0.09	0.61	0.01	<0.01	<0.01	1.18	0.043	0.150	0.018	0.40	0.96	1.69	N.A.
646191	Drill Core	0.01	0.193	19.26	0.09	0.57	0.02	<0.01	<0.01	0.57	0.015	0.079	0.011	0.22	0.87	0.70	N.A.
646192	Drill Core	0.01	0.200	19.87	0.05	0.34	<0.01	<0.01	<0.01	0.63	0.015	0.112	0.013	0.31	1.30	0.71	2.86
646193	Drill Core	<0.01	0.246	20.13	0.05	0.26	<0.01	<0.01	<0.01	0.64	0.017	0.110	0.013	0.26	0.96	0.74	N.A.
646194	Drill Core	<0.01	0.221	19.41	0.06	0.30	0.01	0.02	<0.01	0.59	0.016	0.094	0.012	0.24	0.96	0.67	N.A.

QUALITY CONTROL REPORT

SMI08000569.1

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646194	Drill Core	10.75	<2	8	6	<0.001	0.018	<0.02	<0.01	<2	0.098	0.013	0.14	8.80	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.67
Pulp Duplicates																					
646151	Rock Pulp	0.03	I.S.	I.S.	I.S.	0.002	0.012	<0.02	<0.01	<2	0.084	0.003	0.08	4.61	<0.02	0.02	<0.001	<0.01	<0.01	<0.01	3.54
REP 646151	QC																				
646152	Drill Core	3.89	<2	15	25	<0.001	0.040	<0.02	<0.01	<2	0.099	0.011	0.10	10.11	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	1.51
REP 646152	QC		<2	19	25																
REP 646167	QC																				
646170	Drill Core	10.76	3	34	169	<0.001	0.015	<0.02	<0.01	2	0.109	0.014	0.14	9.41	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.08
REP 646170	QC					<0.001	0.015	<0.02	<0.01	<2	0.109	0.014	0.13	9.35	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.08
646177	Drill Core	11.34	<2	8	3	<0.001	0.008	<0.02	<0.01	3	0.044	0.006	0.10	4.68	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	11.42
REP 646177	QC		<2	6	4																
646180	Drill Core	1.66	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.06	1.00	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	1.78
REP 646180	QC																				
646184	Drill Core	6.20	<2	15	12	<0.001	0.031	<0.02	<0.01	<2	0.036	0.008	0.11	5.77	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	14.30
REP 646184	QC																				
646185	Drill Core	11.64	<2	5	4	<0.001	0.033	<0.02	<0.01	<2	0.033	0.009	0.10	5.48	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	13.34
REP 646185	QC																				
646187	Drill Core	11.41	<2	26	30	<0.001	0.049	<0.02	<0.01	<2	0.125	0.017	0.11	9.15	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	9.12
REP 646187	QC					<0.001	0.048	<0.02	<0.01	<2	0.122	0.016	0.11	9.00	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	8.89
Core Reject Duplicates																					
646167	Drill Core	11.32	4	90	107	<0.001	0.129	<0.02	<0.01	<2	0.258	0.026	0.11	10.90	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.02
DUP 646167	QC		5	75	91	<0.001	0.134	<0.02	<0.01	3	0.261	0.025	0.12	11.28	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.02
Reference Materials																					
STD CDN-PGMS-14	Standard		246	113	427																
STD CDN-PGMS-14	Standard		284	103	415																
STD CDN-PGMS-14	Standard		241	113	416																
STD CSC	Standard																				
STD CSC	Standard																				
STD CSC	Standard																				

QUALITY CONTROL REPORT

SMI08000569.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0	
646194 Drill Core	<0.01	0.221	19.41	0.06	0.30	0.01	0.02	<0.01	0.59	0.016	0.094	0.012	0.24	0.96	0.67	N.A.	
Pulp Duplicates																	
646151 Rock Pulp	0.05	0.078	1.58	0.30	7.59	2.33	1.03	<0.01	0.30	0.008	0.010	<0.001	0.47	0.13	0.26	N.A.	
REP 646151 QC										0.008	0.010	<0.001	0.45	0.12	0.26		
646152 Drill Core	<0.01	0.099	19.76	0.05	0.46	0.01	<0.01	<0.01	1.06	0.035	0.101	0.011	0.32	0.98	1.29	N.A.	
REP 646152 QC																	
REP 646167 QC										0.140	0.275	0.029	1.04	1.90			
646170 Drill Core	<0.01	0.167	23.80	0.02	0.12	<0.01	0.15	<0.01	0.23	0.016	0.115	0.013	0.27	1.73	0.27	N.A.	
REP 646170 QC	<0.01	0.160	23.60	0.02	0.12	<0.01	0.06	<0.01	0.23								
646177 Drill Core	<0.01	0.175	12.75	0.14	0.75	0.06	0.28	<0.01	0.08	0.008	0.036	0.004	0.14	0.41	0.13	N.A.	
REP 646177 QC																	
646180 Drill Core	<0.01	0.002	0.21	0.06	6.87	3.28	1.12	<0.01	<0.01	<0.001	<0.001	<0.001	0.05	0.03	0.03	N.A.	
REP 646180 QC															<0.02		
646184 Drill Core	0.05	0.164	9.95	0.25	0.96	0.08	<0.01	<0.01	0.35	0.033	0.032	0.006	0.25	0.24	0.58	N.A.	
REP 646184 QC										0.035	0.032	0.006	0.27	0.25			
646185 Drill Core	0.02	0.196	10.88	0.18	1.24	0.09	<0.01	<0.01	0.52	0.037	0.029	0.007	0.32	0.28	0.81	N.A.	
REP 646185 QC															0.83		
646187 Drill Core	0.01	0.201	14.36	0.11	0.67	0.06	<0.01	<0.01	1.32	0.048	0.113	0.015	0.46	0.54	1.85	N.A.	
REP 646187 QC	0.02	0.187	13.73	0.11	0.66	0.06	<0.01	<0.01	1.32								
Core Reject Duplicates																	
646167 Drill Core	<0.01	0.166	22.52	0.01	0.07	<0.01	0.17	<0.01	1.82	0.137	0.268	0.028	0.93	1.57	2.33	N.A.	
DUP 646167 QC	<0.01	0.173	22.78	0.01	0.07	<0.01	0.25	<0.01	1.77	0.135	0.255	0.027	0.86	1.45	2.22	N.A.	
Reference Materials																	
STD CDN-PGMS-14 Standard																	
STD CDN-PGMS-14 Standard																	
STD CDN-PGMS-14 Standard																	
STD CSC Standard															4.14		
STD CSC Standard															4.16		
STD CSC Standard															4.23		

QUALITY CONTROL REPORT

SMI08000569.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
		P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																17.29
STD OREAS76A	Standard																17.41
STD OREAS76A	Standard																17.05
STD R3NI	Standard										0.790	0.426	0.059	5.91	0.15		
STD R3NI	Standard										0.806	0.421	0.056	5.17	0.27		
STD R3T	Standard	0.04	0.019	1.70	0.18	2.46	0.32	0.60	0.01	15.09							
STD R3T	Standard	0.03	0.018	1.68	0.17	2.44	0.32	0.60	0.01	14.51							
STD R3T	Standard	0.05	0.019	1.62	0.18	2.42	0.32	0.58	<0.01	16.60							
STD R3T	Standard	0.04	0.020	1.62	0.17	2.38	0.31	0.59	<0.01	15.88							
STD R3T	Standard	0.06	0.019	1.66	0.17	2.42	0.31	0.58	<0.01	15.81							
STD R3T	Standard	0.05	0.018	1.63	0.17	2.38	0.31	0.58	<0.01	15.97							
STD R3T Expected		0.05	0.02	1.64		2.44	0.31	0.59									
STD R3NI Expected												0.42					
STD CSC Expected																	4.19
STD OREAS76A Expected																	18
STD FA10R Expected																	
STD CDN-PGMS-14																	
BLK	Blank																<0.02
BLK	Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01							
BLK	Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	0.31	<0.01	<0.01							
BLK	Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01							
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank																<0.02
BLK	Blank																<0.02
BLK	Blank																

QUALITY CONTROL REPORT

SMI08000569.1

		WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca
		kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2	<0.001	0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.29	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.50
G1	Prep Blank	<0.01	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.28	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.34

QUALITY CONTROL REPORT

SMI08000569.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
		P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
Prep Wash																	
G1	Prep Blank	0.05	<0.001	0.63	0.23	8.35	2.67	3.10	<0.01	0.01	<0.001	<0.001	<0.001	0.10	0.04	<0.02	N.A.
G1	Prep Blank	0.06	<0.001	0.62	0.22	8.21	2.68	3.12	<0.01	<0.01	<0.001	<0.001	<0.001	0.09	0.04	0.02	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Sandy Smeeton
 Receiving Lab: Canada-Smithers
 Received: June 27, 2008
 Report Date: September 12, 2008
 Page: 1 of 2

CERTIFICATE OF ANALYSIS

SMI08000571.2

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-249C
 P.O. Number
 Number of Samples: 22

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	20	Crush split and pulverize drill core to 200 mesh		
3B	21	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
7TD	22	4 Acid digestion ICP-ES analysis.	0.5	Completed
8NiS	22	Leached with H2O2 + NH4 citrate	1	Completed
2A (TOTAL S)	22	Analysis by Leco	0.1	Completed
G8SG	1	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS

Version 2 : Include total S & 3B data with correct standards.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 12, 2008

Page: 2 of 2 Part 1

CERTIFICATE OF ANALYSIS

SMI08000571.2

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646195	Drill Core	10.91	<2	19	16	<0.001	0.013	<0.02	<0.01	<2	0.086	0.012	0.14	8.57	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.58
646196	Drill Core	10.58	<2	11	13	<0.001	0.008	<0.02	<0.01	<2	0.103	0.010	0.15	8.80	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.27
646197	Drill Core	10.48	<2	8	10	<0.001	0.014	<0.02	<0.01	<2	0.150	0.013	0.12	8.36	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.89
646198	Drill Core	10.02	<2	<3	4	<0.001	0.019	<0.02	<0.01	<2	0.093	0.018	0.14	10.26	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.01
646199	Drill Core	10.33	<2	5	7	<0.001	0.019	<0.02	<0.01	<2	0.121	0.018	0.14	8.97	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.60
646200	Rock Pulp	0.02	I.S.	I.S.	I.S.	<0.001	0.046	<0.02	<0.01	<2	0.389	0.027	0.12	12.33	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.11
646201	Rock Pulp	0.03	723	426	1444	0.001	0.012	<0.02	<0.01	<2	0.089	0.003	0.08	4.75	<0.02	0.02	<0.001	<0.01	<0.01	0.01	3.67
646202	Drill Core	10.27	<2	8	3	<0.001	0.017	<0.02	<0.01	<2	0.102	0.015	0.11	8.64	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.60
646203	Drill Core	10.37	<2	12	5	<0.001	0.017	<0.02	<0.01	<2	0.109	0.015	0.15	8.99	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.83
646204	Drill Core	10.07	<2	12	18	<0.001	0.018	<0.02	<0.01	<2	0.130	0.017	0.13	9.07	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.66
646205	Drill Core	10.83	<2	11	17	<0.001	0.019	<0.02	<0.01	<2	0.133	0.014	0.14	9.04	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.30
646206	Drill Core	3.06	<2	<3	3	<0.001	0.006	<0.02	<0.01	<2	0.098	0.010	0.12	7.23	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.67
646207	Drill Core	6.89	<2	<3	<2	<0.001	0.015	<0.02	<0.01	<2	0.094	0.013	0.13	8.58	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.86
646208	Drill Core	9.84	<2	<3	3	<0.001	0.007	<0.02	0.01	<2	0.068	0.009	0.13	6.81	<0.02	0.05	<0.001	<0.01	<0.01	<0.01	3.87
646209	Drill Core	10.35	<2	6	4	<0.001	0.018	<0.02	0.01	<2	0.063	0.010	0.13	8.09	<0.02	0.09	<0.001	<0.01	<0.01	0.02	6.25
646210	Drill Core	2.19	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	1.09	<0.02	0.08	<0.001	<0.01	<0.01	<0.01	1.94
646211	Drill Core	9.00	<2	7	5	<0.001	0.019	<0.02	<0.01	<2	0.051	0.009	0.10	7.61	<0.02	0.03	<0.001	<0.01	<0.01	0.02	6.38
646212	Drill Core	10.28	<2	30	37	<0.001	0.055	<0.02	<0.01	<2	0.068	0.012	0.11	7.63	<0.02	0.04	<0.001	<0.01	<0.01	0.02	9.49
646213	Drill Core	3.78	<2	19	21	<0.001	0.021	<0.02	<0.01	<2	0.067	0.010	0.08	7.91	<0.02	0.03	<0.001	<0.01	<0.01	0.02	3.69
646214	Drill Core	5.99	4	<3	7	<0.001	0.025	<0.02	0.01	<2	0.018	0.007	0.14	8.23	<0.02	0.09	<0.001	<0.01	<0.01	0.04	8.43
646215	Drill Core	9.36	9	5	7	<0.001	0.011	<0.02	0.02	<2	0.018	0.003	0.09	4.23	<0.02	0.06	<0.001	<0.01	<0.01	0.03	5.34
646216	Drill Core	8.72	6	4	3	0.001	0.006	<0.02	0.02	<2	0.018	0.002	0.11	3.51	<0.02	0.04	<0.001	<0.01	<0.01	0.02	3.21



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 12, 2008

Page: 2 of 2 Part 2

CERTIFICATE OF ANALYSIS

SMI08000571.2

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS 2A	Leco	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S		SG
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02		0
646195	Drill Core	<0.01	0.195	19.19	0.08	0.45	0.02	0.01	<0.01	0.45	0.010	0.077	0.010	0.19	0.78	0.63	N.A.
646196	Drill Core	<0.01	0.159	20.35	0.07	0.39	0.02	<0.01	<0.01	0.35	0.006	0.093	0.009	0.20	0.77	0.43	N.A.
646197	Drill Core	<0.01	0.145	19.80	0.07	0.38	0.01	<0.01	<0.01	0.61	0.010	0.136	0.011	0.27	0.95	0.73	N.A.
646198	Drill Core	<0.01	0.149	19.95	0.06	0.36	<0.01	<0.01	<0.01	0.72	0.015	0.082	0.016	0.17	0.82	0.84	N.A.
646199	Drill Core	<0.01	0.217	19.72	0.03	0.24	<0.01	<0.01	<0.01	0.82	0.016	0.106	0.016	0.23	0.91	1.06	N.A.
646200	Rock Pulp	0.01	0.174	19.75	0.02	0.28	0.03	0.10	<0.01	2.75	0.047	0.390	0.024	1.08	1.53	4.21	N.A.
646201	Rock Pulp	0.06	0.080	1.56	0.30	7.12	2.38	1.08	<0.01	0.24	0.009	0.012	<0.001	0.53	0.13	0.24	N.A.
646202	Drill Core	0.01	0.174	20.79	0.03	0.27	<0.01	<0.01	<0.01	0.85	0.012	0.090	0.014	0.18	0.92	1.01	2.80
646203	Drill Core	<0.01	0.200	20.17	0.04	0.33	<0.01	<0.01	<0.01	0.78	0.013	0.097	0.014	0.18	0.92	0.91	N.A.
646204	Drill Core	0.01	0.223	20.02	0.07	0.36	<0.01	<0.01	<0.01	0.92	0.017	0.112	0.015	0.22	0.74	1.17	N.A.
646205	Drill Core	0.04	0.160	17.36	0.09	1.31	<0.01	<0.01	<0.01	0.87	0.019	0.122	0.012	0.33	0.67	1.26	N.A.
646206	Drill Core	<0.01	0.211	18.64	0.04	0.29	<0.01	<0.01	<0.01	0.37	0.006	0.069	0.004	0.36	1.04	0.37	N.A.
646207	Drill Core	<0.01	0.137	18.26	0.05	0.41	<0.01	<0.01	<0.01	0.77	0.015	0.071	0.005	0.40	0.90	0.90	N.A.
646208	Drill Core	<0.01	0.208	15.56	0.04	0.41	<0.01	<0.01	<0.01	0.46	0.006	0.038	0.003	0.38	0.93	0.71	N.A.
646209	Drill Core	0.02	0.135	13.08	0.18	2.06	<0.01	<0.01	<0.01	1.24	0.018	0.028	0.005	0.44	0.90	2.31	N.A.
646210	Drill Core	0.02	0.001	0.25	0.07	7.47	3.53	1.13	<0.01	<0.01	<0.001	<0.001	<0.001	0.06	0.03	<0.02	N.A.
646211	Drill Core	0.04	0.121	12.48	0.20	1.82	0.05	0.02	<0.01	0.98	0.019	0.027	0.005	0.25	0.26	1.82	N.A.
646212	Drill Core	0.02	0.129	11.06	0.19	1.13	0.08	0.03	<0.01	1.13	0.056	0.042	0.006	0.48	0.25	2.05	N.A.
646213	Drill Core	0.03	0.176	13.24	0.19	1.54	0.01	<0.01	<0.01	0.97	0.021	0.036	0.004	0.37	0.50	1.80	N.A.
646214	Drill Core	0.09	0.030	7.82	0.27	3.36	<0.01	0.02	<0.01	2.09	0.027	0.010	0.003	1.59	1.70	3.14	N.A.
646215	Drill Core	0.03	0.041	4.42	0.15	3.76	0.99	0.50	<0.01	1.40	0.011	0.013	0.002	1.20	1.08	1.56	N.A.
646216	Drill Core	0.04	0.018	2.78	0.21	4.91	1.81	0.92	<0.01	1.23	0.005	0.017	0.002	1.40	0.98	1.34	N.A.

QUALITY CONTROL REPORT

SMI08000571.2

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca
Unit	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01
Pulp Duplicates																				
REP G1	QC	<2	<3	<2																
646198	Drill Core	10.02	<2	<3	4	<0.001	0.019	<0.02	<0.01	<2	0.093	0.018	0.14	10.26	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646198	QC																			
646201	Rock Pulp	0.03	723	426	1444	0.001	0.012	<0.02	<0.01	<2	0.089	0.003	0.08	4.75	<0.02	0.02	<0.001	<0.01	<0.01	0.01
REP 646201	QC																			
646212	Drill Core	10.28	<2	30	37	<0.001	0.055	<0.02	<0.01	<2	0.068	0.012	0.11	7.63	<0.02	0.04	<0.001	<0.01	<0.01	0.02
REP 646212	QC																			
646215	Drill Core	9.36	9	5	7	<0.001	0.011	<0.02	0.02	<2	0.018	0.003	0.09	4.23	<0.02	0.06	<0.001	<0.01	<0.01	0.03
REP 646215	QC																			
Core Reject Duplicates																				
646210	Drill Core	2.19	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	1.09	<0.02	0.08	<0.001	<0.01	<0.01	<0.01
DUP 646210	QC		<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	1.26	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
Reference Materials																				
STD CDN-PGMS-14	Standard		227	105	429															
STD CSC	Standard																			
STD CSC	Standard																			
STD FA10R	Standard		477	469	481															
STD OREAS76A	Standard																			
STD OREAS76A	Standard																			
STD R3NI	Standard																			
STD R3NI	Standard																			
STD R3T	Standard					0.077	0.810	1.97	4.11	192	0.535	0.060	0.09	32.76	<0.02	<0.01	0.023	0.03	<0.01	0.02
STD R3T	Standard					0.076	0.792	1.93	4.10	191	0.523	0.060	0.09	31.84	<0.02	<0.01	0.023	0.03	<0.01	0.02
STD R3T	Standard					0.078	0.837	2.08	4.21	222	0.553	0.063	0.09	33.52	0.02	<0.01	0.024	0.04	<0.01	0.02
STD R3T	Standard					0.076	0.835	2.02	4.22	214	0.542	0.062	0.09	33.08	0.02	<0.01	0.024	0.04	<0.01	0.02
STD R3NI Expected																				
STD R3T Expected						0.077	0.805	1.98	4.1	190	0.525	0.061	0.09	34.17	0.04	0.01	0.024	0.04		2.23
STD CSC Expected																				

QUALITY CONTROL REPORT

SMI08000571.2

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS 2A	Leco	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S		Cu	Ni	Co	Fe	Mg	TOT/S	SG
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
Pulp Duplicates																	
REP G1	QC																
646198	Drill Core	<0.01	0.149	19.95	0.06	0.36	<0.01	<0.01	<0.01	0.72	0.015	0.082	0.016	0.17	0.82	0.84	N.A.
REP 646198	QC																
646201	Rock Pulp	0.06	0.080	1.56	0.30	7.12	2.38	1.08	<0.01	0.24	0.009	0.012	<0.001	0.53	0.13	0.24	N.A.
REP 646201	QC										0.008	0.011	<0.001	0.58	0.17		
646212	Drill Core	0.02	0.129	11.06	0.19	1.13	0.08	0.03	<0.01	1.13	0.056	0.042	0.006	0.48	0.25	2.05	N.A.
REP 646212	QC										0.054	0.041	0.006	0.44	0.23		
646215	Drill Core	0.03	0.041	4.42	0.15	3.76	0.99	0.50	<0.01	1.40	0.011	0.013	0.002	1.20	1.08	1.56	N.A.
REP 646215	QC																
Core Reject Duplicates																	
646210	Drill Core	0.02	0.001	0.25	0.07	7.47	3.53	1.13	<0.01	<0.01	<0.001	<0.001	<0.001	0.06	0.03	<0.02	N.A.
DUP 646210	QC	0.02	<0.001	0.26	0.07	7.99	3.49	1.16	<0.01	<0.01	<0.001	<0.001	<0.001	0.07	0.05	<0.02	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CSC	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																
STD OREAS76A	Standard																
STD R3NI	Standard										0.704	0.410	0.054	6.07	0.14		
STD R3NI	Standard										0.806	0.421	0.056	5.17	0.27		
STD R3T	Standard	0.06	0.019	1.66	0.17	2.42	0.31	0.58	<0.01	15.81							
STD R3T	Standard	0.05	0.018	1.63	0.17	2.38	0.31	0.58	<0.01	15.97							
STD R3T	Standard	0.05	0.021	1.69	0.18	2.48	0.32	0.61	<0.01	16.18							
STD R3T	Standard	0.05	0.020	1.67	0.18	2.44	0.32	0.60	<0.01	15.83							
STD R3NI Expected														0.42			
STD R3T Expected		0.05	0.02	1.64		2.44	0.31	0.59									
STD CSC Expected																	

QUALITY CONTROL REPORT

SMI08000571.2

		WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca
		kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01
STD OREAS76A Expected																					
STD FA10R Expected			485	472	476																
STD CDN-PGMS-14			259	119	451																
BLK	Blank																				
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank																				
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank																				
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.19	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.30
G1	Prep Blank	<0.01				<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.30	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.31
G1	Prep Blank		<2	<3	<2																

QUALITY CONTROL REPORT

SMI08000571.2

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS 2A Leco	G8SG	
		P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
STD OREAS76A Expected																	18
STD FA10R Expected																	
STD CDN-PGMS-14																	
BLK	Blank																<0.02
BLK	Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01							
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01							
BLK	Blank																<0.02
BLK	Blank																
BLK	Blank																
Prep Wash																	
G1	Prep Blank	0.07	0.001	0.59	0.22	7.41	2.61	1.68	<0.01	<0.01	<0.001	<0.001	<0.001	0.07	0.03	N.A.	N.A.
G1	Prep Blank	0.08	0.001	0.66	0.24	7.78	2.56	1.40	<0.01	<0.01	<0.001	<0.001	<0.001	0.06	0.02	N.A.	N.A.
G1	Prep Blank																

Hole 08-250



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Sandy Smeeton
 Receiving Lab: Canada-Smithers
 Received: June 27, 2008
 Report Date: August 19, 2008
 Page: 1 of 2

CERTIFICATE OF ANALYSIS

SMI08000572.2

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-250A
 P.O. Number
 Number of Samples: 28

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	26	Crush split and pulverize drill core to 200 mesh		
3B	28	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
7TD	28	4 Acid digestion ICP-ES analysis.	0.5	Completed
8NiS	28	Leached with H2O2 + NH4 citrate	1	Completed
2A (Total S)	28	Analysis by Leco	0.1	Completed
G8SG	2	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS

Version 2 : G3B- Au, Pt and Pd and G2A total S for all samples included.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: August 19, 2008

Page: 2 of 2 Part 1

CERTIFICATE OF ANALYSIS

SMI08000572.2

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646217	Drill Core	12.36	<2	16	18	<0.001	0.006	<0.02	<0.01	<2	0.155	0.012	0.14	7.80	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.84
646218	Drill Core	9.99	<2	18	23	<0.001	0.006	<0.02	<0.01	<2	0.166	0.013	0.14	9.24	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.43
646219	Drill Core	10.64	<2	15	6	<0.001	0.007	<0.02	0.01	<2	0.162	0.013	0.14	9.17	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.71
646220A	Drill Core	12.35	<2	4	2	<0.001	0.005	<0.02	<0.01	<2	0.161	0.013	0.17	10.34	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.58
646220B	Drill Core	12.50	<2	<3	4	<0.001	0.005	<0.02	<0.01	<2	0.173	0.014	0.18	11.06	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.42
646221	Drill Core	12.50	<2	5	7	<0.001	0.002	<0.02	<0.01	<2	0.187	0.015	0.17	10.48	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.11
646222	Drill Core	12.09	<2	12	12	<0.001	0.001	<0.02	<0.01	<2	0.192	0.015	0.16	10.54	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.11
646223	Drill Core	11.87	<2	13	8	<0.001	0.005	<0.02	<0.01	<2	0.172	0.014	0.16	9.82	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.11
646224	Drill Core	12.54	<2	3	<2	<0.001	0.003	<0.02	<0.01	<2	0.191	0.014	0.15	10.83	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.05
646225	Drill Core	0.02	I.S.	I.S.	I.S.	<0.001	0.055	<0.02	0.02	<2	0.233	0.011	0.10	8.92	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	4.27
646226	Drill Core	0.02	I.S.	I.S.	I.S.	0.001	0.048	<0.02	<0.01	<2	0.401	0.027	0.12	12.98	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.14
646227	Drill Core	12.44	<2	7	6	<0.001	0.031	<0.02	<0.01	<2	0.147	0.013	0.15	10.38	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.50
646228	Drill Core	13.13	<2	6	<2	<0.001	0.001	<0.02	<0.01	<2	0.187	0.014	0.14	9.15	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.15
646229	Drill Core	11.09	<2	4	3	<0.001	0.002	<0.02	<0.01	<2	0.172	0.013	0.12	8.03	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.03
646230	Drill Core	11.29	<2	<3	3	<0.001	0.005	<0.02	<0.01	<2	0.144	0.011	0.13	8.30	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	3.21
646231	Drill Core	11.71	<2	11	7	<0.001	0.001	<0.02	<0.01	<2	0.176	0.013	0.16	9.09	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.08
646232	Drill Core	10.96	<2	<3	3	<0.001	0.002	<0.02	<0.01	<2	0.154	0.012	0.16	8.78	<0.02	0.02	<0.001	<0.01	<0.01	<0.01	0.96
646233	Drill Core	10.31	<2	4	3	<0.001	0.002	<0.02	<0.01	<2	0.158	0.013	0.15	9.88	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.32
646234	Drill Core	11.27	<2	12	7	<0.001	0.001	<0.02	<0.01	<2	0.156	0.013	0.17	9.30	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.85
646235	Drill Core	11.82	<2	17	18	<0.001	0.001	<0.02	<0.01	<2	0.165	0.014	0.15	9.14	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.21
646236	Drill Core	11.83	<2	15	14	<0.001	0.002	<0.02	<0.01	<2	0.157	0.013	0.13	8.80	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.21
646237	Drill Core	11.00	<2	20	22	<0.001	0.002	<0.02	<0.01	<2	0.150	0.013	0.14	9.62	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.59
646238	Drill Core	10.31	<2	<3	<2	<0.001	0.005	<0.02	<0.01	<2	0.140	0.012	0.14	8.82	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.83
646239	Drill Core	10.98	<2	12	7	<0.001	0.002	<0.02	<0.01	<2	0.176	0.014	0.13	9.55	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.02
646240	Drill Core	2.22	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	1.11	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	1.72
646241	Drill Core	11.63	<2	4	2	<0.001	0.003	<0.02	<0.01	<2	0.188	0.014	0.15	10.08	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.55
646242	Drill Core	11.04	<2	<3	2	<0.001	0.001	<0.02	<0.01	<2	0.189	0.014	0.15	8.99	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.12
646243	Drill Core	11.68	<2	3	3	<0.001	<0.001	<0.02	<0.01	<2	0.188	0.014	0.17	9.67	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.10



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: August 19, 2008

Page: 2 of 2 Part 2

CERTIFICATE OF ANALYSIS

SMI08000572.2

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0	
646217	Drill Core	<0.01	0.084	22.21	0.08	0.53	0.04	0.03	<0.01	0.11	0.005	0.142	0.010	0.30	1.58	0.16	N.A.
646218	Drill Core	<0.01	0.094	22.57	0.05	0.32	<0.01	0.01	<0.01	0.12	0.004	0.147	0.010	0.31	1.68	0.15	N.A.
646219	Drill Core	<0.01	0.475	22.84	0.06	0.52	<0.01	0.01	<0.01	0.12	0.007	0.139	0.009	0.23	1.14	0.12	N.A.
646220A	Drill Core	<0.01	0.176	24.79	0.09	0.49	<0.01	0.03	<0.01	0.10	0.005	0.123	0.009	0.28	1.47	0.10	N.A.
646220B	Drill Core	<0.01	0.193	24.63	0.08	0.41	<0.01	0.02	<0.01	0.12	0.004	0.127	0.009	0.28	1.53	0.12	N.A.
646221	Drill Core	<0.01	0.206	25.69	0.04	0.21	<0.01	<0.01	<0.01	0.09	0.002	0.113	0.008	0.28	1.30	0.09	N.A.
646222	Drill Core	<0.01	0.161	25.65	0.06	0.23	<0.01	<0.01	<0.01	0.09	0.001	0.119	0.008	0.36	1.63	0.10	3.05
646223	Drill Core	0.01	0.159	24.36	0.10	0.61	<0.01	<0.01	<0.01	0.10	0.005	0.114	0.008	0.31	1.41	0.10	N.A.
646224	Drill Core	<0.01	0.161	25.74	0.04	0.18	<0.01	<0.01	<0.01	0.12	0.003	0.143	0.009	0.26	1.34	0.08	N.A.
646225	Drill Core	<0.01	0.998	13.70	0.19	4.05	0.33	0.12	<0.01	0.45	0.051	0.180	0.007	0.36	0.34	0.42	N.A.
646226	Drill Core	<0.01	0.179	21.72	0.02	0.29	0.03	0.10	<0.01	2.65	0.046	0.389	0.025	1.24	1.92	4.25	N.A.
646227	Drill Core	<0.01	0.161	23.99	0.10	0.33	<0.01	<0.01	<0.01	0.15	0.030	0.123	0.009	0.28	1.76	0.15	N.A.
646228	Drill Core	<0.01	0.154	24.48	0.04	0.21	<0.01	<0.01	<0.01	0.10	0.002	0.143	0.009	0.27	1.38	0.13	N.A.
646229	Drill Core	<0.01	0.145	24.53	0.04	0.20	<0.01	<0.01	<0.01	0.11	0.002	0.152	0.010	0.24	1.56	0.13	N.A.
646230	Drill Core	0.02	0.136	20.23	0.21	1.29	0.01	<0.01	<0.01	0.09	0.005	0.127	0.008	0.22	1.17	0.10	N.A.
646231	Drill Core	<0.01	0.160	25.61	0.04	0.27	<0.01	<0.01	<0.01	0.10	0.001	0.119	0.008	0.25	1.34	0.10	N.A.
646232	Drill Core	<0.01	0.147	23.29	0.07	0.69	<0.01	0.04	<0.01	0.08	0.002	0.111	0.007	0.26	1.40	0.09	2.83
646233	Drill Core	<0.01	0.200	24.01	0.06	0.33	<0.01	<0.01	<0.01	0.09	0.002	0.124	0.009	0.27	1.49	0.09	N.A.
646234	Drill Core	<0.01	0.249	23.77	0.10	0.51	<0.01	<0.01	<0.01	0.07	0.002	0.087	0.006	0.33	1.46	0.08	N.A.
646235	Drill Core	<0.01	0.241	25.56	0.04	0.21	<0.01	<0.01	<0.01	0.08	0.001	0.108	0.008	0.31	1.57	0.11	N.A.
646236	Drill Core	<0.01	0.095	24.46	0.08	0.40	<0.01	<0.01	<0.01	0.07	0.002	0.097	0.007	0.28	1.47	0.06	N.A.
646237	Drill Core	0.02	0.212	23.88	0.09	0.65	<0.01	<0.01	<0.01	0.07	0.002	0.085	0.006	0.29	1.43	0.05	N.A.
646238	Drill Core	0.02	0.235	21.84	0.14	0.93	<0.01	<0.01	<0.01	0.09	0.005	0.111	0.008	0.23	1.42	0.08	N.A.
646239	Drill Core	<0.01	0.275	24.14	0.04	0.27	<0.01	<0.01	<0.01	0.11	0.003	0.172	0.011	0.23	1.76	0.10	N.A.
646240	Drill Core	0.01	0.002	0.23	0.06	6.05	3.31	1.03	<0.01	<0.01	<0.001	<0.001	<0.001	0.11	0.05	<0.02	N.A.
646241	Drill Core	<0.01	0.150	25.06	0.06	0.41	0.01	0.01	<0.01	0.08	0.003	0.131	0.008	0.30	1.44	0.10	N.A.
646242	Drill Core	<0.01	0.119	25.40	0.05	0.32	<0.01	<0.01	<0.01	0.09	0.001	0.125	0.008	0.27	1.29	0.09	N.A.
646243	Drill Core	<0.01	0.141	25.72	0.06	0.24	<0.01	<0.01	<0.01	0.06	<0.001	0.091	0.006	0.26	1.15	0.07	N.A.

QUALITY CONTROL REPORT

SMI08000572.2

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646238	Drill Core	10.31	<2	<3	<2	<0.001	0.005	<0.02	<0.01	<2	0.140	0.012	0.14	8.82	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.83
Pulp Duplicates																					
REP 646232	QC																				
646239	Drill Core	10.98	<2	12	7	<0.001	0.002	<0.02	<0.01	<2	0.176	0.014	0.13	9.55	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.02
REP 646239	QC					<0.001	0.003	<0.02	<0.01	<2	0.182	0.014	0.13	9.86	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.03
Core Reject Duplicates																					
646232	Drill Core	10.96	<2	<3	3	<0.001	0.002	<0.02	<0.01	<2	0.154	0.012	0.16	8.78	<0.02	0.02	<0.001	<0.01	<0.01	<0.01	0.96
DUP 646232	QC		<2	4	5	<0.001	0.001	<0.02	<0.01	<2	0.178	0.014	0.15	9.25	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.34
Reference Materials																					
STD CDN-PGMS-14	Standard		288	119	432																
STD CDN-PGMS-14	Standard		227	105	429																
STD CSC	Standard																				
STD CSC	Standard																				
STD CSC	Standard																				
STD FA10R	Standard		473	466	475																
STD FA10R	Standard		477	469	481																
STD OREAS76A	Standard																				
STD OREAS76A	Standard																				
STD OREAS76A	Standard																				
STD R3NI	Standard																				
STD R3NI	Standard																				
STD R3T	Standard					0.078	0.837	2.08	4.21	222	0.553	0.063	0.09	33.52	0.02	<0.01	0.024	0.04	<0.01	0.02	2.29
STD R3T	Standard					0.076	0.835	2.02	4.22	214	0.542	0.062	0.09	33.08	0.02	<0.01	0.024	0.04	<0.01	0.02	2.27
STD R3T Expected						0.077	0.805	1.98	4.1	190	0.525	0.061	0.09	34.17	0.04	0.01	0.024	0.04			2.23
STD R3NI Expected																					
STD CSC Expected																					
STD OREAS76A Expected																					
STD FA10R Expected			485	472	476																
STD CDN-PGMS-14			259	119	451																

QUALITY CONTROL REPORT

SMI08000572.2

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S		Cu	Ni	Co	Fe	Mg	TOT/S	SG
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
646238	Drill Core	0.02	0.235	21.84	0.14	0.93	<0.01	<0.01	<0.01	0.09	0.005	0.111	0.008	0.23	1.42	0.08	N.A.
Pulp Duplicates																	
REP 646232	QC										0.002	0.116	0.008	0.29	1.53		
646239	Drill Core	<0.01	0.275	24.14	0.04	0.27	<0.01	<0.01	<0.01	0.11	0.003	0.172	0.011	0.23	1.76	0.10	N.A.
REP 646239	QC	<0.01	0.271	25.34	0.04	0.28	<0.01	<0.01	<0.01	0.14							
Core Reject Duplicates																	
646232	Drill Core	<0.01	0.147	23.29	0.07	0.69	<0.01	0.04	<0.01	0.08	0.002	0.111	0.007	0.26	1.40	0.09	2.83
DUP 646232	QC	<0.01	0.151	25.60	0.04	0.29	<0.01	<0.01	<0.01	0.09	0.002	0.120	0.008	0.28	1.46	0.09	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard																4.14
STD CSC	Standard																4.07
STD CSC	Standard																4.29
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																17.29
STD OREAS76A	Standard																18.19
STD OREAS76A	Standard																17.85
STD R3NI	Standard										0.704	0.410	0.054	6.07	0.14		
STD R3NI	Standard										0.749	0.416	0.055	4.44	0.14		
STD R3T	Standard	0.05	0.021	1.69	0.18	2.48	0.32	0.61	<0.01	16.18							
STD R3T	Standard	0.05	0.020	1.67	0.18	2.44	0.32	0.60	<0.01	15.83							
STD R3T Expected		0.05	0.02	1.64		2.44	0.31	0.59									
STD R3NI Expected												0.42					
STD CSC Expected																	4.19
STD OREAS76A Expected																	18
STD FA10R Expected																	
STD CDN-PGMS-14																	

QUALITY CONTROL REPORT

SMI08000572.2

		WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca
		kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01
BLK	Blank																				
BLK	Blank																				
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank																				
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank																				
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.21	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.25
G1	Prep Blank	<0.01	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.21	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.34

QUALITY CONTROL REPORT

SMI08000572.2

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
		P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
BLK	Blank																<0.02
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01							
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank																
BLK	Blank																<0.02
BLK	Blank																<0.02
BLK	Blank																
BLK	Blank																
Prep Wash																	
G1	Prep Blank	0.07	<0.001	0.66	0.22	7.56	2.55	2.98	<0.01	<0.01	<0.001	<0.001	<0.001	0.12	0.05	N.A.	N.A.
G1	Prep Blank	0.07	<0.001	0.65	0.21	7.76	2.56	3.05	<0.01	<0.01	<0.001	<0.001	<0.001	0.08	0.03	N.A.	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Sandy Smeeton
 Receiving Lab: Canada-Smithers
 Received: July 03, 2008
 Report Date: September 16, 2008
 Page: 1 of 2

CERTIFICATE OF ANALYSIS

SMI08000580.4

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-250B
 P.O. Number
 Number of Samples: 23

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	21	Crush split and pulverize drill core to 200 mesh		
3B	21	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
7TD	23	4 Acid digestion ICP-ES analysis.	0.5	Completed
8NiS	23	Leached with H2O2 + NH4 citrate	1	Completed
2A (Total S)	23	Analysis by Leco	0.1	Completed
G8SG	2	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS

Version 4 : 3B-Au,Pt,Pd data with correct standards included.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 16, 2008

Page: 2 of 2 Part 1

CERTIFICATE OF ANALYSIS

SMI08000580.4

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646244	Drill Core	11.37	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	0.177	0.014	0.16	8.98	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.42
646245	Drill Core	11.47	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	0.169	0.014	0.15	8.57	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.16
646246	Drill Core	11.34	<2	<3	3	<0.001	0.001	<0.02	<0.01	<2	0.161	0.013	0.15	8.56	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.29
646247	Drill Core	11.13	<2	31	26	<0.001	0.003	<0.02	<0.01	<2	0.174	0.013	0.14	9.19	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.12
646248	Drill Core	10.88	<2	19	12	<0.001	0.002	<0.02	<0.01	<2	0.188	0.014	0.15	8.24	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.08
646249	Drill Core	11.48	<2	10	10	<0.001	0.003	<0.02	<0.01	<2	0.175	0.014	0.16	8.53	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.36
646250	Rock Pulp	0.05	I.S.	I.S.	I.S.	0.001	0.011	<0.02	<0.01	2	0.084	0.003	0.08	4.46	<0.02	0.02	<0.001	<0.01	<0.01	0.01	3.64
646251	Rock Pulp	0.04	I.S.	I.S.	I.S.	0.001	0.045	<0.02	<0.01	<2	0.392	0.026	0.12	11.50	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.13
646252	Drill Core	11.71	<2	6	3	<0.001	0.004	<0.02	<0.01	<2	0.180	0.014	0.15	9.14	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.27
646253	Drill Core	11.24	<2	5	3	<0.001	0.001	<0.02	<0.01	<2	0.201	0.014	0.15	8.36	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.14
646254	Drill Core	11.57	<2	6	5	<0.001	0.002	<0.02	<0.01	<2	0.208	0.014	0.15	8.49	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.05
646255	Drill Core	10.87	<2	5	3	<0.001	0.002	<0.02	<0.01	<2	0.202	0.014	0.15	8.77	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.03
646256	Drill Core	11.06	<2	6	4	<0.001	0.006	<0.02	<0.01	<2	0.192	0.013	0.15	8.84	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.16
646257	Drill Core	11.26	<2	<3	5	<0.001	0.003	<0.02	<0.01	<2	0.217	0.014	0.16	9.28	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.30
646258	Drill Core	11.23	<2	6	9	<0.001	0.003	<0.02	<0.01	<2	0.207	0.014	0.16	8.63	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.12
646259	Drill Core	10.66	<2	10	5	<0.001	0.005	<0.02	<0.01	<2	0.183	0.013	0.15	8.45	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.16
646260	Drill Core	10.28	<2	<3	5	<0.001	0.005	<0.02	<0.01	<2	0.180	0.014	0.16	8.77	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.67
646261	Drill Core	11.45	<2	4	7	<0.001	0.006	<0.02	<0.01	<2	0.178	0.012	0.16	8.51	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.42
646262	Drill Core	11.77	<2	3	4	<0.001	0.005	<0.02	<0.01	<2	0.173	0.013	0.15	8.57	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.91
646263	Drill Core	10.12	<2	18	5	<0.001	0.006	<0.02	<0.01	<2	0.167	0.014	0.15	9.40	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.36
646264	Drill Core	11.91	<2	<3	3	<0.001	0.004	<0.02	<0.01	<2	0.165	0.013	0.16	9.27	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.93
646265	Drill Core	11.36	<2	<3	5	<0.001	0.006	<0.02	<0.01	<2	0.158	0.012	0.16	8.41	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.68
646266	Drill Core	5.43	<2	11	15	<0.001	0.005	<0.02	<0.01	<2	0.196	0.014	0.17	8.36	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.48



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 16, 2008

Page: 2 of 2 Part 2

CERTIFICATE OF ANALYSIS

SMI08000580.4

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS 2A Leco	G8SG	
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0	
646244	Drill Core	0.01	0.126	23.16	0.05	0.28	0.01	0.01	<0.01	0.04	<0.001	0.073	0.004	0.35	1.52	0.06	N.A.
646245	Drill Core	<0.01	0.127	22.81	0.04	0.25	<0.01	<0.01	<0.01	0.06	0.001	0.094	0.006	0.27	1.36	0.10	N.A.
646246	Drill Core	<0.01	0.119	22.33	0.05	0.28	<0.01	<0.01	<0.01	0.06	0.001	0.099	0.007	0.28	1.39	0.08	N.A.
646247	Drill Core	<0.01	0.144	22.55	0.04	0.23	<0.01	<0.01	<0.01	0.08	0.004	0.131	0.009	0.26	1.34	0.09	N.A.
646248	Drill Core	<0.01	0.110	23.27	0.05	0.25	<0.01	<0.01	<0.01	0.08	0.002	0.126	0.008	0.30	1.61	0.07	N.A.
646249	Drill Core	<0.01	0.126	22.75	0.05	0.27	<0.01	<0.01	<0.01	0.06	0.002	0.100	0.007	0.24	1.22	0.07	N.A.
646250	Rock Pulp	0.05	0.081	1.61	0.30	7.95	2.30	1.05	<0.01	0.24	0.010	0.012	<0.001	0.72	0.14	0.25	N.A.
646251	Rock Pulp	<0.01	0.174	19.53	0.02	0.27	0.03	0.09	<0.01	2.69	0.050	0.408	0.026	1.35	1.92	3.99	N.A.
646252	Drill Core	<0.01	0.123	22.29	0.04	0.17	<0.01	<0.01	<0.01	0.11	0.004	0.147	0.010	0.23	1.49	0.10	3.00
646253	Drill Core	<0.01	0.109	23.64	0.04	0.20	<0.01	<0.01	<0.01	0.08	0.002	0.128	0.008	0.38	1.82	0.07	N.A.
646254	Drill Core	<0.01	0.098	23.06	0.04	0.20	<0.01	<0.01	<0.01	0.12	0.002	0.169	0.010	0.29	1.43	0.15	N.A.
646255	Drill Core	<0.01	0.106	23.39	0.04	0.18	<0.01	<0.01	<0.01	0.10	0.002	0.164	0.010	0.28	1.31	0.10	N.A.
646256	Drill Core	0.01	0.124	21.31	0.07	0.65	<0.01	0.02	<0.01	0.11	0.006	0.155	0.009	0.30	1.37	0.13	N.A.
646257	Drill Core	<0.01	0.084	22.95	0.04	0.20	<0.01	<0.01	<0.01	0.10	0.003	0.142	0.008	0.32	1.34	0.12	N.A.
646258	Drill Core	<0.01	0.118	23.10	0.04	0.20	<0.01	<0.01	<0.01	0.12	0.003	0.160	0.009	0.32	1.39	0.13	N.A.
646259	Drill Core	<0.01	0.184	22.01	0.06	0.34	0.01	<0.01	<0.01	0.14	0.005	0.159	0.010	0.34	1.68	0.13	N.A.
646260	Drill Core	<0.01	0.131	22.46	0.08	0.47	<0.01	<0.01	<0.01	0.11	0.005	0.128	0.009	0.33	1.31	0.12	N.A.
646261	Drill Core	<0.01	0.133	21.54	0.09	0.65	<0.01	<0.01	<0.01	0.11	0.006	0.139	0.009	0.35	1.53	0.10	N.A.
646262	Drill Core	<0.01	0.131	21.24	0.08	0.44	<0.01	<0.01	<0.01	0.13	0.005	0.147	0.010	0.31	1.57	0.12	3.05
646263	Drill Core	<0.01	0.154	21.95	0.07	0.47	<0.01	<0.01	<0.01	0.18	0.005	0.151	0.011	0.26	1.31	0.19	N.A.
646264	Drill Core	0.01	0.123	21.52	0.08	0.66	<0.01	<0.01	<0.01	0.13	0.004	0.125	0.009	0.31	1.49	0.12	N.A.
646265	Drill Core	0.02	0.086	20.01	0.11	1.34	<0.01	0.02	<0.01	0.12	0.006	0.136	0.009	0.31	1.27	0.16	N.A.
646266	Drill Core	<0.01	0.093	22.60	0.08	0.28	<0.01	<0.01	<0.01	0.12	0.005	0.140	0.009	0.31	1.17	0.13	N.A.

QUALITY CONTROL REPORT

SMI08000580.4

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
Pulp Duplicates																					
646252	Drill Core	11.71	<2	6	3	<0.001	0.004	<0.02	<0.01	<2	0.180	0.014	0.15	9.14	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.27
REP 646252	QC		I.S.	I.S.	I.S.																
646253	Drill Core	11.24	<2	5	3	<0.001	0.001	<0.02	<0.01	<2	0.201	0.014	0.15	8.36	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.14
REP 646253	QC					<0.001	0.002	<0.02	<0.01	<2	0.201	0.014	0.15	8.40	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.14
646262	Drill Core	11.77	<2	3	4	<0.001	0.005	<0.02	<0.01	<2	0.173	0.013	0.15	8.57	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.91
REP 646262	QC																				
Core Reject Duplicates																					
646261	Drill Core	11.45	<2	4	7	<0.001	0.006	<0.02	<0.01	<2	0.178	0.012	0.16	8.51	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.42
DUP 646261	QC		<2	7	6	<0.001	0.005	<0.02	<0.01	<2	0.171	0.012	0.15	8.41	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.39
Reference Materials																					
STD CDN-PGMS-14	Standard		288	119	432																
STD CDN-PGMS-14	Standard		231	137	420																
STD CDN-PGMS-14	Standard		239	101	420																
STD CSC	Standard																				
STD CSC	Standard																				
STD CSC	Standard																				
STD FA10R	Standard		473	466	475																
STD FA10R	Standard		467	458	459																
STD FA10R	Standard		489	475	488																
STD OREAS76A	Standard																				
STD OREAS76A	Standard																				
STD OREAS76A	Standard																				
STD R3NI	Standard																				
STD R3T	Standard					0.076	0.797	1.94	4.08	196	0.525	0.060	0.09	29.94	0.02	<0.01	0.023	0.03	<0.01	0.02	2.18
STD R3T	Standard					0.076	0.802	1.96	4.06	195	0.526	0.059	0.09	30.06	<0.02	<0.01	0.023	0.03	<0.01	0.02	2.18
STD R3T Expected						0.077	0.805	1.98	4.1	190	0.525	0.061	0.09	34.17	0.04	0.01	0.024	0.04			2.23
STD R3NI Expected																					
STD CSC Expected																					

QUALITY CONTROL REPORT

SMI08000580.4

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS 2A Leco	G8SG	
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S		Cu	Ni	Co	Fe	Mg	TOT/S	SG
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
Pulp Duplicates																	
646252	Drill Core	<0.01	0.123	22.29	0.04	0.17	<0.01	<0.01	<0.01	0.11	0.004	0.147	0.010	0.23	1.49	0.10	3.00
REP 646252	QC																
646253	Drill Core	<0.01	0.109	23.64	0.04	0.20	<0.01	<0.01	<0.01	0.08	0.002	0.128	0.008	0.38	1.82	0.07	N.A.
REP 646253	QC	<0.01	0.107	22.96	0.04	0.20	<0.01	<0.01	<0.01	0.08	0.002	0.124	0.007	0.37	1.71		
646262	Drill Core	<0.01	0.131	21.24	0.08	0.44	<0.01	<0.01	<0.01	0.13	0.005	0.147	0.010	0.31	1.57	0.12	3.05
REP 646262	QC															0.11	
Core Reject Duplicates																	
646261	Drill Core	<0.01	0.133	21.54	0.09	0.65	<0.01	<0.01	<0.01	0.11	0.006	0.139	0.009	0.35	1.53	0.10	N.A.
DUP 646261	QC	<0.01	0.141	20.82	0.09	0.64	<0.01	<0.01	<0.01	0.11	0.006	0.134	0.008	0.29	1.20	0.11	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard																4.24
STD CSC	Standard																4.31
STD CSC	Standard																4.29
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																17.10
STD OREAS76A	Standard																17.92
STD OREAS76A	Standard																17.85
STD R3NI	Standard										0.801	0.428	0.056	6.49	0.20		
STD R3T	Standard	0.06	0.020	1.62	0.17	2.40	0.31	0.58	<0.01	14.99							
STD R3T	Standard	0.05	0.020	1.63	0.17	2.40	0.31	0.58	<0.01	14.86							
STD R3T Expected		0.05	0.02	1.64		2.44	0.31	0.59									
STD R3NI Expected												0.42					
STD CSC Expected																	4.19

QUALITY CONTROL REPORT

SMI08000580.4

	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
STD OREAS76A Expected																					
STD FA10R Expected		485	472	476																	
STD CDN-PGMS-14		259	119	451																	
BLK	Blank																				
BLK	Blank				<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	
BLK	Blank																				
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
BLK	Blank																				
BLK	Blank																				
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2	0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.16	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.30
G1	Prep Blank	<0.01	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.01	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.34

QUALITY CONTROL REPORT

SMI08000580.4

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS 2A Leco	G8SG	
		P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg TOT/S	SG	
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	
STD OREAS76A Expected																18	
STD FA10R Expected																	
STD CDN-PGMS-14																	
BLK	Blank															<0.02	
BLK	Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01							
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank																
BLK	Blank															<0.02	
BLK	Blank															<0.02	
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
Prep Wash																	
G1	Prep Blank	0.07	0.001	0.59	0.21	7.70	2.48	2.91	<0.01	<0.01	<0.001	<0.001	<0.001	0.19	0.05	N.A.	N.A.
G1	Prep Blank	0.07	<0.001	0.59	0.21	7.63	2.59	2.97	<0.01	<0.01	<0.001	<0.001	<0.001	0.12	0.04	N.A.	N.A.

Hole 08-251

Hole 08-252



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Sandy Smeeton
 Receiving Lab: Canada-Smithers
 Received: July 03, 2008
 Report Date: October 08, 2008
 Page: 1 of 2

CERTIFICATE OF ANALYSIS

SMI08000581.2

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C05-252A
 P.O. Number
 Number of Samples: 25

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC: Email Distribution List

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	23	Crush split and pulverize drill core to 200 mesh		
3B	25	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
7TD	25	4 Acid digestion ICP-ES analysis.	0.5	Completed
8NiS	25	Leached with H2O2 + NH4 citrate	1	Completed
2A (TOTAL S)	25	Analysis by Leco	0.1	Completed
G8SG	2	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS

Version 2 : Reanalysis of Au, Pt and Pd with proper control stds. Total S for all samples.



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 08, 2008

Page: 2 of 2 Part 1

CERTIFICATE OF ANALYSIS

SMI08000581.2

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646267	Drill Core	9.24	5	75	100	<0.001	0.014	<0.02	<0.01	<2	0.139	0.015	0.14	8.65	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.28
646268	Drill Core	11.46	5	55	76	<0.001	0.072	<0.02	<0.01	<2	0.191	0.021	0.15	10.64	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.03
646269	Drill Core	12.09	7	123	140	<0.001	0.131	<0.02	<0.01	<2	0.314	0.029	0.12	10.87	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.14
646270	Drill Core	2.33	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	0.001	<0.001	0.07	1.32	<0.02	0.08	<0.001	<0.01	<0.01	<0.01	2.02
646271	Drill Core	10.76	5	50	71	<0.001	0.013	<0.02	<0.01	<2	0.154	0.014	0.14	9.25	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.44
646272	Drill Core	11.72	18	29	33	<0.001	0.003	<0.02	<0.01	<2	0.189	0.015	0.15	9.07	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.08
646273	Drill Core	11.07	21	57	56	<0.001	0.009	<0.02	<0.01	2	0.163	0.014	0.13	8.95	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.06
646274	Drill Core	11.58	20	29	29	<0.001	0.004	<0.02	<0.01	<2	0.146	0.013	0.15	9.07	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.46
646275	Rock Pulp	0.07	I.S.	I.S.	I.S.	<0.001	0.012	<0.02	<0.01	2	0.084	0.003	0.08	4.75	<0.02	0.02	<0.001	<0.01	<0.01	<0.01	3.69
646276	Rock Pulp	0.04	I.S.	I.S.	I.S.	<0.001	0.029	<0.02	<0.01	<2	0.235	0.016	0.11	8.57	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.69
646277	Drill Core	11.61	26	22	17	<0.001	0.004	<0.02	<0.01	<2	0.149	0.013	0.15	8.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.76
646278	Drill Core	10.65	<2	19	20	<0.001	0.003	<0.02	<0.01	<2	0.138	0.013	0.15	9.00	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.05
646279	Drill Core	11.34	3	7	5	<0.001	0.002	<0.02	<0.01	<2	0.144	0.014	0.14	9.40	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.05
646280A	Drill Core	11.22	<2	10	9	<0.001	0.011	<0.02	<0.01	<2	0.123	0.012	0.15	9.29	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.59
646280B	Drill Core	<0.01	<2	20	9	<0.001	0.010	<0.02	<0.01	<2	0.128	0.013	0.15	9.50	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.43
646281	Drill Core	11.00	7	15	10	<0.001	0.001	<0.02	<0.01	<2	0.152	0.014	0.16	9.74	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.42
646282	Drill Core	11.00	28	10	9	<0.001	0.002	<0.02	<0.01	<2	0.156	0.014	0.16	9.89	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.72
646283	Drill Core	11.00	9	11	4	<0.001	0.003	<0.02	<0.01	<2	0.147	0.014	0.15	9.70	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.93
646284	Drill Core	11.11	<2	15	8	<0.001	0.006	<0.02	<0.01	<2	0.141	0.014	0.15	9.72	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.60
646285	Drill Core	11.07	5	8	8	<0.001	0.001	<0.02	<0.01	<2	0.133	0.013	0.15	9.25	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.49
646286	Drill Core	10.97	19	40	21	<0.001	0.002	<0.02	<0.01	<2	0.149	0.014	0.16	10.59	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.85
646287	Drill Core	10.15	<2	33	36	<0.001	0.002	<0.02	<0.01	3	0.151	0.014	0.15	9.45	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.14
646288	Drill Core	11.58	4	27	28	<0.001	0.002	<0.02	<0.01	<2	0.156	0.014	0.15	10.14	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.67
646289	Drill Core	10.25	46	122	93	<0.001	0.003	<0.02	<0.01	<2	0.166	0.014	0.15	9.47	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.56
646290	Drill Core	10.46	<2	20	25	<0.001	0.002	<0.02	<0.01	<2	0.185	0.015	0.14	9.12	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.09



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 08, 2008

Page: 2 of 2 Part 2

CERTIFICATE OF ANALYSIS

SMI08000581.2

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS 2A	Leco	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0	
646267	Drill Core	<0.01	0.159	24.87	0.02	0.38	0.03	<0.01	<0.01	0.12	0.014	0.133	0.013	0.25	1.47	0.15	N.A.
646268	Drill Core	<0.01	0.174	25.95	0.01	0.08	<0.01	<0.01	<0.01	0.50	0.079	0.195	0.018	0.49	1.61	0.65	N.A.
646269	Drill Core	<0.01	0.177	25.56	0.02	0.15	<0.01	<0.01	<0.01	1.15	0.137	0.319	0.027	0.75	1.51	1.42	N.A.
646270	Drill Core	0.01	<0.001	0.29	0.08	8.19	3.68	1.29	<0.01	<0.01	<0.001	<0.001	<0.001	0.05	0.03	<0.02	N.A.
646271	Drill Core	<0.01	0.240	25.70	0.02	0.12	<0.01	<0.01	<0.01	0.07	0.014	0.109	0.007	0.26	1.98	0.09	N.A.
646272	Drill Core	<0.01	0.181	26.66	0.01	0.09	<0.01	<0.01	<0.01	0.09	0.003	0.153	0.009	0.22	1.54	0.10	3.03
646273	Drill Core	<0.01	0.147	24.99	0.01	0.09	<0.01	<0.01	<0.01	0.13	0.011	0.170	0.012	0.22	1.42	0.14	N.A.
646274	Drill Core	0.01	0.128	22.71	0.03	0.51	<0.01	<0.01	<0.01	0.07	0.004	0.122	0.009	0.18	1.39	0.09	N.A.
646275	Rock Pulp	0.05	0.080	1.56	0.31	7.71	2.37	1.09	<0.01	0.25	0.009	0.012	<0.001	0.50	0.12	0.26	N.A.
646276	Rock Pulp	<0.01	0.176	25.07	0.02	0.30	<0.01	0.07	<0.01	1.06	0.031	0.231	0.013	0.90	2.51	1.35	N.A.
646277	Drill Core	<0.01	0.142	23.47	0.04	0.19	<0.01	<0.01	<0.01	0.08	0.005	0.114	0.008	0.22	1.51	0.09	N.A.
646278	Drill Core	0.01	0.163	22.50	0.03	0.79	<0.01	<0.01	<0.01	0.10	0.003	0.131	0.011	0.20	1.19	0.13	N.A.
646279	Drill Core	<0.01	0.223	24.95	0.01	0.06	<0.01	<0.01	<0.01	0.10	0.002	0.144	0.011	0.16	1.19	0.11	N.A.
646280A	Drill Core	0.02	0.186	20.77	0.16	1.19	0.05	0.26	<0.01	0.10	0.011	0.117	0.010	0.18	0.97	0.11	N.A.
646280B	Drill Core	0.02	0.215	20.95	0.14	1.10	0.05	0.26	<0.01	0.10	0.010	0.119	0.009	0.17	0.88	0.10	N.A.
646281	Drill Core	<0.01	0.210	25.60	0.02	0.09	<0.01	<0.01	<0.01	0.08	0.001	0.122	0.009	0.15	1.27	0.08	N.A.
646282	Drill Core	<0.01	0.270	24.90	0.01	0.08	<0.01	<0.01	<0.01	0.03	0.001	0.073	0.005	0.11	1.13	0.04	2.99
646283	Drill Core	<0.01	0.275	24.33	0.02	0.10	<0.01	<0.01	<0.01	0.04	0.003	0.082	0.006	0.10	1.23	0.05	N.A.
646284	Drill Core	<0.01	0.233	24.19	0.02	0.10	<0.01	<0.01	<0.01	0.07	0.006	0.113	0.009	0.14	1.22	0.08	N.A.
646285	Drill Core	<0.01	0.225	22.48	0.02	0.25	<0.01	<0.01	<0.01	0.09	0.002	0.116	0.009	0.19	1.63	0.09	N.A.
646286	Drill Core	<0.01	0.291	24.27	0.03	0.17	<0.01	<0.01	<0.01	0.09	0.001	0.098	0.008	0.25	1.53	0.10	N.A.
646287	Drill Core	<0.01	0.177	23.91	0.02	0.11	<0.01	<0.01	<0.01	0.11	0.002	0.148	0.011	0.18	1.17	0.11	N.A.
646288	Drill Core	<0.01	0.143	24.51	0.03	0.14	<0.01	<0.01	<0.01	0.09	0.002	0.134	0.010	0.15	1.13	0.09	N.A.
646289	Drill Core	0.01	0.188	24.41	0.03	0.23	<0.01	<0.01	<0.01	0.11	0.003	0.143	0.010	0.20	1.20	0.10	N.A.
646290	Drill Core	<0.01	0.203	25.78	0.05	0.29	<0.01	<0.01	<0.01	0.13	0.002	0.171	0.011	0.20	1.52	0.13	N.A.

QUALITY CONTROL REPORT

SMI08000581.2

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646270	Drill Core	2.33	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	0.001	<0.001	0.07	1.32	<0.02	0.08	<0.001	<0.01	<0.01	<0.01	2.02
Pulp Duplicates																					
REP G1	QC				<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.30	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	<0.01	2.30
646267	Drill Core	9.24	5	75	100	<0.001	0.014	<0.02	<0.01	<2	0.139	0.015	0.14	8.65	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.28
REP 646267																					
646271	Drill Core	10.76	5	50	71	<0.001	0.013	<0.02	<0.01	<2	0.154	0.014	0.14	9.25	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.44
REP 646271																					
646282	Drill Core	11.00	28	10	9	<0.001	0.002	<0.02	<0.01	<2	0.156	0.014	0.16	9.89	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.72
REP 646282																					
646284	Drill Core	11.11	<2	15	8	<0.001	0.006	<0.02	<0.01	<2	0.141	0.014	0.15	9.72	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.60
REP 646284																					
Reference Materials																					
STD CDN-PGMS-14	Standard		296	110	426																
STD CDN-PGMS-14	Standard		242	110	418																
STD CDN-PGMS-8	Standard		848	390	1411																
STD CSC	Standard																				
STD CSC	Standard																				
STD FA10R	Standard		440	431	450																
STD FA10R	Standard		430	432	440																
STD FA10R	Standard		476	445	486																
STD FA10R	Standard		436	443	443																
STD FA10R	Standard		458	450	468																
STD OREAS76A	Standard																				
STD OREAS76A	Standard																				
STD R3NI	Standard																				
STD R3NI	Standard																				
STD R3T	Standard				0.078	0.813	1.99	4.19	211	0.537	0.060	0.09	32.48	0.02	<0.01	0.023	0.04	<0.01	0.02	2.20	
STD R3T	Standard				0.079	0.817	2.03	4.22	215	0.554	0.061	0.09	33.17	0.02	<0.01	0.024	0.04	<0.01	0.02	2.25	
STD R3NI Expected																					

QUALITY CONTROL REPORT

SMI08000581.2

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS 2A Leco	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
646270 Drill Core	0.01	<0.001	0.29	0.08	8.19	3.68	1.29	<0.01	<0.01	<0.001	<0.001	<0.001	0.05	0.03	<0.02	N.A.
Pulp Duplicates																
REP G1 QC	0.07	<0.001	0.66	0.23	8.10	2.60	2.49	<0.01	<0.01							
646267 Drill Core	<0.01	0.159	24.87	0.02	0.38	0.03	<0.01	<0.01	0.12	0.014	0.133	0.013	0.25	1.47	0.15	N.A.
REP 646267 QC										0.014	0.130	0.012	0.24	1.44		
646271 Drill Core	<0.01	0.240	25.70	0.02	0.12	<0.01	<0.01	<0.01	0.07	0.014	0.109	0.007	0.26	1.98	0.09	N.A.
REP 646271 QC																
646282 Drill Core	<0.01	0.270	24.90	0.01	0.08	<0.01	<0.01	<0.01	0.03	0.001	0.073	0.005	0.11	1.13	0.04	2.99
REP 646282 QC															0.04	
646284 Drill Core	<0.01	0.233	24.19	0.02	0.10	<0.01	<0.01	<0.01	0.07	0.006	0.113	0.009	0.14	1.22	0.08	N.A.
REP 646284 QC										0.006	0.113	0.009	0.13	1.21		
Reference Materials																
STD CDN-PGMS-14 Standard																
STD CDN-PGMS-14 Standard																
STD CDN-PGMS-8 Standard																
STD CSC Standard															4.24	
STD CSC Standard															4.37	
STD FA10R Standard																
STD FA10R Standard																
STD FA10R Standard																
STD FA10R Standard																
STD FA10R Standard																
STD OREAS76A Standard															17.10	
STD OREAS76A Standard															16.88	
STD R3NI Standard										0.801	0.428	0.056	6.49	0.20		
STD R3NI Standard										0.775	0.414	0.053	5.01	0.12		
STD R3T Standard	0.05	0.017	1.65	0.17	2.44	0.31	0.58	0.01	16.15							
STD R3T Standard	0.05	0.020	1.68	0.18	2.49	0.32	0.60	<0.01	16.21							
STD R3NI Expected															0.42	

QUALITY CONTROL REPORT

SMI08000581.2

	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
STD R3T Expected					0.077	0.805	1.98	4.1	190	0.525	0.061	0.09	34.17	0.04	0.01	0.024	0.04			2.23	
STD CSC Expected																					
STD OREAS76A Expected																					
STD CDN-PGMS-14		259	119	451																	
STD FA10R Expected		485	472	476																	
STD CDN-PGMS-8 Expected		820	440	1500																	
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
BLK	Blank				<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01
BLK	Blank																				
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2																
G1	Prep Blank	<0.01	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.23	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.31
G1	Prep Blank				<0.001	<0.001	<0.02	<0.01	3	<0.001	<0.001	0.07	2.31	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	<0.01	2.30

QUALITY CONTROL REPORT

SMI08000581.2

	7TD P	7TD Cr	7TD Mg	7TD Ti	7TD Al	7TD Na	7TD K	7TD W	7TD S	8NiS Cu	8NiS Ni	8NiS Co	8NiS Fe	8NiS 2A Leco Mg	G8SG TOT/S	SG
	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
STD R3T Expected	0.05	0.02	1.64		2.44	0.31	0.59									
STD CSC Expected															4.19	
STD OREAS76A Expected															18	
STD CDN-PGMS-14																
STD FA10R Expected																
STD CDN-PGMS-8 Expected																
BLK Blank															<0.02	
BLK Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01							
BLK Blank															<0.02	
BLK Blank																
BLK Blank																
BLK Blank																
BLK Blank																
BLK Blank																
BLK Blank																
BLK Blank																
Prep Wash																
G1 Prep Blank										<0.001	<0.001	<0.001	0.09	0.02	<0.02	N.A.
G1 Prep Blank	0.07	<0.001	0.62	0.22	7.68	2.59	2.85	<0.01	<0.01	<0.001	<0.001	<0.001	0.07	0.02	<0.02	N.A.
G1 Prep Blank	0.07	<0.001	0.64	0.23	8.17	2.63	2.83	<0.01	0.01							



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By:
 Receiving Lab: Canada-Smithers
 Received: July 10, 2008
 Report Date: August 19, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000606.2

CLIENT JOB INFORMATION

Project: Turnagain Ni
 Shipment ID: C08-252B
 P.O. Number
 Number of Samples: 52

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	48	Crush split and pulverize drill core to 200 mesh		
3B	51	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
7TD	52	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	52	Leached with H2O2 + NH4 citrate	1	Completed
2A (Total S)	52	Analysis by Leco	0.1	Completed
Specific Gravity	3	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS

Version 2 : G2A total S for all samples included.

Invoice To: **Hard Creek Nickel Corporation**
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain Ni
 Report Date: August 19, 2008

Page: 2 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000606.2

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646291	Drill Core	10.31	103	21	14	<0.001	0.004	<0.02	<0.01	<2	0.132	0.010	0.11	6.32	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	4.41
646292	Drill Core	10.98	16	27	25	<0.001	0.005	<0.02	<0.01	<2	0.189	0.014	0.13	7.80	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.14
646293	Drill Core	11.78	40	51	41	<0.001	0.013	<0.02	<0.01	<2	0.161	0.014	0.14	9.24	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	2.38
646294	Drill Core	11.60	4	22	36	<0.001	0.002	<0.02	<0.01	<2	0.183	0.014	0.13	7.88	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.51
646295	Drill Core	10.77	<2	19	17	<0.001	0.002	<0.02	<0.01	<2	0.165	0.014	0.13	7.59	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.88
646296	Drill Core	12.61	<2	26	24	<0.001	0.002	<0.02	<0.01	<2	0.179	0.014	0.13	7.62	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.40
646297	Drill Core	11.40	<2	6	9	<0.001	0.002	<0.02	<0.01	<2	0.146	0.013	0.12	7.42	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.46
646298	Drill Core	11.61	<2	16	32	<0.001	0.007	<0.02	<0.01	<2	0.164	0.014	0.13	7.62	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.39
646299	Drill Core	10.07	2	34	36	<0.001	0.006	<0.02	<0.01	<2	0.152	0.013	0.12	7.46	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.22
646300	Rock Pulp	0.03	I.S.	I.S.	I.S.	<0.001	0.044	<0.02	<0.01	<2	0.395	0.025	0.12	12.95	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.12
646301	Rock Pulp	0.04	710	446	1439	0.001	0.012	<0.02	<0.01	<2	0.089	0.003	0.08	5.01	<0.02	0.02	<0.001	<0.01	<0.01	<0.01	3.68
646302	Drill Core	11.57	3	15	13	<0.001	0.013	<0.02	<0.01	<2	0.107	0.010	0.11	6.04	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	6.22
646303	Drill Core	12.45	2	23	14	<0.001	0.007	<0.02	<0.01	<2	0.049	0.006	0.08	3.77	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	11.90
646304	Drill Core	11.31	<2	21	23	<0.001	0.006	<0.02	<0.01	<2	0.070	0.007	0.09	4.79	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	10.08
646305	Drill Core	11.21	<2	11	11	<0.001	0.010	<0.02	<0.01	<2	0.055	0.007	0.10	5.31	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	11.89
646306	Drill Core	10.59	<2	24	18	<0.001	0.005	<0.02	<0.01	<2	0.126	0.012	0.11	6.62	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	4.63
646307	Drill Core	11.14	5	35	32	<0.001	0.004	<0.02	<0.01	<2	0.160	0.014	0.13	7.64	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.13
646308	Drill Core	11.36	3	25	23	<0.001	0.015	<0.02	<0.01	<2	0.111	0.011	0.12	7.61	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	6.76
646309	Drill Core	11.14	5	24	14	<0.001	0.002	<0.02	<0.01	<2	0.180	0.015	0.13	8.71	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.77
646310A	Drill Core	10.83	4	16	21	<0.001	0.006	<0.02	<0.01	<2	0.124	0.011	0.14	7.87	<0.02	0.03	<0.001	<0.01	<0.01	<0.01	4.74
646310B	Drill Core		4	18	17	<0.001	0.006	<0.02	<0.01	<2	0.125	0.012	0.14	7.96	<0.02	0.03	<0.001	<0.01	<0.01	<0.01	4.51
646311	Drill Core	10.06	2	17	12	<0.001	0.003	<0.02	<0.01	<2	0.150	0.013	0.13	8.84	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.18
646312	Drill Core	10.37	<2	15	12	<0.001	0.003	<0.02	<0.01	<2	0.131	0.012	0.14	8.66	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.14
646313	Drill Core	10.58	2	39	28	<0.001	0.003	<0.02	<0.01	<2	0.132	0.012	0.14	9.00	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.43
646314	Drill Core	11.23	2	65	50	<0.001	0.007	<0.02	<0.01	<2	0.134	0.012	0.14	8.98	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.80
646315	Drill Core	10.88	<2	13	10	<0.001	0.004	<0.02	<0.01	<2	0.153	0.014	0.16	10.10	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.07
646316	Drill Core	10.62	2	41	44	<0.001	0.005	<0.02	<0.01	<2	0.128	0.013	0.15	10.14	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.18
646317	Drill Core	11.07	2	9	13	<0.001	0.013	<0.02	<0.01	<2	0.072	0.010	0.13	8.32	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	7.79
646318	Drill Core	11.94	2	18	12	<0.001	0.004	<0.02	<0.01	<2	0.127	0.013	0.15	10.11	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.41
646319	Drill Core	10.16	<2	27	18	<0.001	0.003	<0.02	<0.01	<2	0.131	0.012	0.14	9.31	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.04



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain Ni
 Report Date: August 19, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000606.2

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%		
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0	
646291	Drill Core	<0.01	0.218	20.74	0.09	0.54	0.02	<0.01	<0.01	0.09	0.004	0.114	0.007	0.22	1.38	0.10	N.A.
646292	Drill Core	<0.01	0.173	25.61	0.02	0.14	<0.01	0.01	<0.01	0.09	0.004	0.109	0.007	0.30	1.63	0.08	N.A.
646293	Drill Core	<0.01	0.053	23.13	0.21	0.91	0.04	0.03	<0.01	0.12	0.013	0.076	0.006	0.37	1.19	0.13	N.A.
646294	Drill Core	<0.01	0.036	25.56	0.02	0.16	0.01	0.01	<0.01	0.08	0.002	0.083	0.006	0.41	1.66	0.08	N.A.
646295	Drill Core	<0.01	0.028	25.23	0.05	0.48	0.02	0.09	<0.01	0.05	0.002	0.077	0.005	0.30	1.26	0.08	N.A.
646296	Drill Core	<0.01	0.092	25.88	0.03	0.28	0.01	0.02	<0.01	0.04	0.002	0.084	0.004	0.25	1.15	0.05	N.A.
646297	Drill Core	<0.01	0.151	24.31	0.05	0.72	0.01	0.06	<0.01	0.04	0.002	0.084	0.005	0.26	1.27	0.04	N.A.
646298	Drill Core	<0.01	0.184	26.08	0.03	0.30	<0.01	<0.01	<0.01	0.04	0.007	0.065	0.004	0.30	1.19	0.05	N.A.
646299	Drill Core	0.01	0.125	24.59	0.05	0.70	0.01	0.11	<0.01	0.05	0.005	0.077	0.005	0.34	1.36	0.04	N.A.
646300	Rock Pulp	<0.01	0.181	21.55	0.02	0.27	0.03	0.08	<0.01	2.58	0.048	0.395	0.024	1.20	1.76	4.08	N.A.
646301	Rock Pulp	0.05	0.095	1.69	0.31	8.14	2.36	1.29	<0.01	0.26	0.009	0.012	<0.001	0.43	0.12	0.28	N.A.
646302	Drill Core	<0.01	0.179	21.49	0.06	0.33	0.03	<0.01	<0.01	0.04	0.011	0.050	0.004	0.22	0.78	0.05	3.18
646303	Drill Core	<0.01	0.240	13.50	0.07	0.44	0.08	<0.01	<0.01	<0.01	0.007	0.032	0.002	0.11	0.46	0.04	N.A.
646304	Drill Core	<0.01	0.194	15.78	0.12	0.65	0.06	<0.01	<0.01	0.03	0.006	0.051	0.004	0.13	0.50	0.06	N.A.
646305	Drill Core	<0.01	0.147	13.38	0.18	1.16	0.05	<0.01	<0.01	0.02	0.010	0.043	0.004	0.13	0.41	0.08	N.A.
646306	Drill Core	<0.01	0.168	21.87	0.05	0.26	0.03	<0.01	<0.01	0.07	0.005	0.092	0.007	0.17	0.85	0.09	N.A.
646307	Drill Core	<0.01	0.145	24.49	0.03	0.17	0.01	<0.01	<0.01	0.09	0.004	0.119	0.008	0.20	0.95	0.10	N.A.
646308	Drill Core	<0.01	0.109	18.87	0.16	0.72	0.03	<0.01	<0.01	0.08	0.015	0.071	0.006	0.22	0.82	0.10	N.A.
646309	Drill Core	<0.01	0.186	25.00	0.03	0.16	0.01	<0.01	<0.01	0.08	0.002	0.119	0.008	0.22	1.04	0.09	N.A.
646310A	Drill Core	0.04	0.114	19.43	0.12	1.98	<0.01	<0.01	<0.01	0.17	0.006	0.117	0.008	0.19	0.60	0.17	N.A.
646310B	Drill Core	0.04	0.111	19.00	0.11	1.92	<0.01	<0.01	<0.01	0.17	0.006	0.114	0.008	0.22	0.78	0.17	N.A.
646311	Drill Core	<0.01	0.119	22.46	0.07	0.56	0.01	<0.01	<0.01	0.11	0.003	0.132	0.009	0.18	0.77	0.13	N.A.
646312	Drill Core	0.01	0.102	21.05	0.11	1.06	0.01	0.04	<0.01	0.09	0.003	0.120	0.009	0.17	0.63	0.11	N.A.
646313	Drill Core	<0.01	0.054	20.97	0.12	0.80	0.01	<0.01	<0.01	0.09	0.004	0.110	0.008	0.19	0.79	0.10	N.A.
646314	Drill Core	<0.01	0.093	20.62	0.07	0.49	0.02	0.02	<0.01	0.10	0.006	0.109	0.008	0.17	0.69	0.11	N.A.
646315	Drill Core	0.01	0.164	22.69	0.07	0.36	0.01	<0.01	<0.01	0.10	0.004	0.116	0.008	0.19	0.83	0.15	N.A.
646316	Drill Core	<0.01	0.132	21.05	0.07	0.41	0.02	<0.01	<0.01	0.09	0.004	0.096	0.008	0.19	0.87	0.12	N.A.
646317	Drill Core	0.01	0.072	15.29	0.43	2.09	0.03	<0.01	<0.01	0.16	0.013	0.059	0.006	0.18	0.51	0.25	N.A.
646318	Drill Core	0.02	0.100	21.53	0.09	0.73	0.01	<0.01	<0.01	0.08	0.003	0.094	0.008	0.18	0.70	0.08	N.A.
646319	Drill Core	0.01	0.100	21.31	0.07	0.58	0.01	0.02	<0.01	0.14	0.003	0.100	0.008	0.22	0.67	0.19	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain Ni
 Report Date: August 19, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000606.2

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646320	Drill Core	10.45	<2	22	16	<0.001	0.003	<0.02	<0.01	<2	0.122	0.012	0.13	9.25	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.17
646321	Drill Core	11.56	4	124	127	<0.001	0.004	<0.02	<0.01	<2	0.149	0.013	0.15	9.73	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.65
646322	Drill Core	11.09	2	140	172	<0.001	0.018	<0.02	<0.01	<2	0.156	0.014	0.14	10.26	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.42
646323	Drill Core	10.20	<2	44	52	<0.001	0.004	<0.02	<0.01	<2	0.121	0.012	0.12	9.43	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.43
646324	Drill Core	6.80	<2	46	55	<0.001	0.005	<0.02	<0.01	<2	0.113	0.012	0.13	8.71	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.74
646325	Rock Pulp	0.02	1197	388	1454	<0.001	0.012	<0.02	<0.01	<2	0.085	0.003	0.07	4.82	<0.02	0.02	<0.001	<0.01	<0.01	0.01	3.49
646326	Rock Pulp	<0.01	<2	13	<2	<0.001	0.029	<0.02	<0.01	<2	0.236	0.015	0.10	8.50	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.66
646327	Drill Core	3.82	4	30	38	<0.001	0.051	<0.02	<0.01	<2	0.097	0.011	0.12	8.39	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	5.16
646328	Drill Core	10.87	<2	13	12	<0.001	0.026	<0.02	<0.01	<2	0.108	0.012	0.12	8.33	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	4.07
646329	Drill Core	11.32	11	<3	<2	<0.001	0.036	<0.02	<0.01	<2	0.118	0.013	0.12	8.94	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.51
646330	Drill Core	1.94	<2	65	101	<0.001	<0.001	<0.02	<0.01	<2	0.001	<0.001	0.06	1.11	<0.02	0.08	<0.001	<0.01	<0.01	<0.01	1.87
646331	Drill Core	11.84	3	130	119	<0.001	0.050	<0.02	<0.01	<2	0.076	0.009	0.11	6.70	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	9.35
646332	Drill Core	5.36	4	138	139	<0.001	0.092	<0.02	<0.01	<2	0.151	0.015	0.11	8.92	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.36
646333	Drill Core	5.48	<2	45	48	<0.001	0.056	<0.02	0.01	<2	0.121	0.015	0.14	8.79	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.94
646334	Drill Core	10.47	<2	72	73	<0.001	0.077	<0.02	<0.01	<2	0.208	0.021	0.13	10.27	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.62
646335	Drill Core	11.06	<2	42	50	<0.001	0.118	<0.02	<0.01	<2	0.264	0.028	0.13	12.67	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.27
646336	Drill Core	11.41	<2	35	35	<0.001	0.061	<0.02	<0.01	<2	0.173	0.021	0.13	10.56	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.34
646337	Drill Core	11.30	4	14	15	<0.001	0.031	<0.02	<0.01	<2	0.059	0.011	0.10	6.82	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	6.89
646338	Drill Core	6.19	8	<3	5	<0.001	0.013	<0.02	0.02	<2	0.063	0.008	0.15	10.56	<0.02	<0.01	<0.001	<0.01	<0.01	0.08	1.37
646339	Drill Core	2.23	11	<3	3	<0.001	<0.001	<0.02	0.03	<2	0.026	0.003	0.11	7.48	<0.02	<0.01	<0.001	<0.01	<0.01	0.03	0.43
646340A	Drill Core	5.51	4	<3	3	<0.001	0.008	<0.02	0.01	<2	0.087	0.008	0.14	6.09	<0.02	0.04	<0.001	<0.01	<0.01	<0.01	6.59
646340B	Drill Core		7	<3	3	<0.001	0.008	<0.02	0.01	<2	0.084	0.008	0.13	5.78	<0.02	0.04	<0.001	<0.01	<0.01	<0.01	6.34



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain Ni
 Report Date: August 19, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000606.2

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0	
646320	Drill Core	0.01	0.125	20.14	0.10	0.72	<0.01	0.02	<0.01	0.20	0.004	0.094	0.008	0.27	0.73	0.29	N.A.
646321	Drill Core	<0.01	0.154	22.83	0.06	0.33	<0.01	0.01	<0.01	0.12	0.003	0.101	0.008	0.24	0.82	0.16	N.A.
646322	Drill Core	<0.01	0.175	22.18	0.06	0.33	<0.01	<0.01	<0.01	0.14	0.018	0.147	0.011	0.24	0.77	0.17	2.77
646323	Drill Core	<0.01	0.172	19.31	0.07	0.42	<0.01	0.01	<0.01	0.10	0.004	0.110	0.010	0.19	0.68	0.13	N.A.
646324	Drill Core	<0.01	0.151	19.18	0.10	0.49	<0.01	0.01	<0.01	0.07	0.004	0.102	0.010	0.12	0.46	0.09	N.A.
646325	Rock Pulp	0.05	0.085	1.58	0.29	7.78	2.22	1.06	<0.01	0.23	0.008	0.011	<0.001	0.43	0.11	0.23	N.A.
646326	Rock Pulp	<0.01	0.142	21.66	0.02	0.30	<0.01	0.07	<0.01	0.98	0.029	0.226	0.012	0.75	2.03	1.25	N.A.
646327	Drill Core	<0.01	0.156	17.44	0.20	0.98	0.04	0.03	<0.01	0.11	0.051	0.085	0.008	0.17	0.59	0.21	N.A.
646328	Drill Core	<0.01	0.159	18.01	0.12	0.66	0.03	0.02	<0.01	0.43	0.026	0.103	0.011	0.21	0.60	0.47	N.A.
646329	Drill Core	<0.01	0.154	17.03	0.09	0.41	0.03	<0.01	<0.01	0.59	0.038	0.122	0.012	0.34	1.11	0.71	N.A.
646330	Drill Core	0.01	0.002	0.31	0.07	7.33	3.36	1.06	<0.01	<0.01	<0.001	<0.001	<0.001	0.03	0.04	<0.02	N.A.
646331	Drill Core	<0.01	0.140	12.32	0.17	0.76	0.06	<0.01	<0.01	0.60	0.060	0.076	0.008	0.30	0.41	0.85	N.A.
646332	Drill Core	<0.01	0.114	17.78	0.06	0.33	0.02	<0.01	<0.01	0.72	0.101	0.163	0.014	0.34	0.57	0.92	2.93
646333	Drill Core	<0.01	0.160	17.98	0.11	0.52	0.03	<0.01	<0.01	0.54	0.056	0.116	0.013	0.24	0.47	0.63	N.A.
646334	Drill Core	<0.01	0.149	20.06	0.05	0.28	<0.01	<0.01	<0.01	0.93	0.076	0.213	0.019	0.37	0.57	1.30	N.A.
646335	Drill Core	<0.01	0.150	18.59	0.06	0.31	<0.01	<0.01	<0.01	1.72	0.115	0.247	0.025	0.72	0.51	2.64	N.A.
646336	Drill Core	<0.01	0.169	19.18	0.06	0.29	<0.01	<0.01	<0.01	1.05	0.061	0.164	0.017	0.46	0.72	1.44	N.A.
646337	Drill Core	<0.01	0.134	12.22	0.08	0.65	0.01	<0.01	<0.01	0.83	0.029	0.036	0.004	0.52	1.01	1.35	N.A.
646338	Drill Core	0.09	0.064	12.08	0.87	5.39	<0.01	<0.01	<0.01	0.48	0.012	0.029	0.003	0.46	0.61	0.60	N.A.
646339	Drill Core	0.08	0.021	11.20	0.08	8.26	<0.01	<0.01	<0.01	<0.01	<0.001	0.006	<0.001	0.19	0.24	0.03	N.A.
646340A	Drill Core	0.02	0.132	11.05	0.03	1.77	0.13	0.29	<0.01	0.99	0.007	0.062	0.004	0.87	1.51	1.23	N.A.
646340B	Drill Core	0.02	0.128	10.77	0.03	1.70	0.13	0.26	<0.01	0.90	0.007	0.061	0.003	0.78	1.37	1.22	N.A.

QUALITY CONTROL REPORT

SMI08000606.2

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
Pulp Duplicates																					
646294	Drill Core	11.60	4	22	36	<0.001	0.002	<0.02	<0.01	<2	0.183	0.014	0.13	7.88	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.51
REP 646294	QC																				
646297	Drill Core	11.40	<2	6	9	<0.001	0.002	<0.02	<0.01	<2	0.146	0.013	0.12	7.42	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.46
REP 646297	QC																				
646310B	Drill Core		4	18	17	<0.001	0.006	<0.02	<0.01	<2	0.125	0.012	0.14	7.96	<0.02	0.03	<0.001	<0.01	<0.01	<0.01	4.51
REP 646310B	QC																				
646317	Drill Core	11.07	2	9	13	<0.001	0.013	<0.02	<0.01	<2	0.072	0.010	0.13	8.32	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	7.79
REP 646317	QC		<2	12	14																
646321	Drill Core	11.56	4	124	127	<0.001	0.004	<0.02	<0.01	<2	0.149	0.013	0.15	9.73	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.65
REP 646321	QC					<0.001	0.003	<0.02	<0.01	<2	0.142	0.013	0.14	9.55	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.59
646327	Drill Core	3.82	4	30	38	<0.001	0.051	<0.02	<0.01	<2	0.097	0.011	0.12	8.39	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	5.16
REP 646327	QC																				
646335	Drill Core	11.06	<2	42	50	<0.001	0.118	<0.02	<0.01	<2	0.264	0.028	0.13	12.67	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.27
REP 646335	QC																				
Core Reject Duplicates																					
646299	Drill Core	10.07	2	34	36	<0.001	0.006	<0.02	<0.01	<2	0.152	0.013	0.12	7.46	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.22
DUP 646299	QC		<2	34	36	<0.001	0.006	<0.02	<0.01	<2	0.153	0.013	0.12	7.24	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.25
646333	Drill Core	5.48	<2	45	48	<0.001	0.056	<0.02	0.01	<2	0.121	0.015	0.14	8.79	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.94
DUP 646333	QC		<2	62	56	<0.001	0.054	<0.02	<0.01	<2	0.114	0.014	0.13	8.51	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.81
Reference Materials																					
STD CDN-PGMS-14	Standard		212	96	421																
STD CDN-PGMS-14	Standard		275	105	426																
STD CDN-PGMS-14	Standard		275	102	406																
STD CSC	Standard																				
STD CSC	Standard																				
STD CSC	Standard																				
STD CSC	Standard																				
STD FA10R	Standard		445	441	440																

QUALITY CONTROL REPORT

SMI08000606.2

Method		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
Analyte		P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG
Unit		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
Pulp Duplicates																	
646294	Drill Core	<0.01	0.036	25.56	0.02	0.16	0.01	0.01	<0.01	0.08	0.002	0.083	0.006	0.41	1.66	0.08	N.A.
REP 646294	QC															0.08	
646297	Drill Core	<0.01	0.151	24.31	0.05	0.72	0.01	0.06	<0.01	0.04	0.002	0.084	0.005	0.26	1.27	0.04	N.A.
REP 646297	QC										0.003	0.084	0.005	0.27	1.32		
646310B	Drill Core	0.04	0.111	19.00	0.11	1.92	<0.01	<0.01	<0.01	0.17	0.006	0.114	0.008	0.22	0.78	0.17	N.A.
REP 646310B	QC										0.006	0.118	0.009	0.22	0.80		
646317	Drill Core	0.01	0.072	15.29	0.43	2.09	0.03	<0.01	<0.01	0.16	0.013	0.059	0.006	0.18	0.51	0.25	N.A.
REP 646317	QC																
646321	Drill Core	<0.01	0.154	22.83	0.06	0.33	<0.01	0.01	<0.01	0.12	0.003	0.101	0.008	0.24	0.82	0.16	N.A.
REP 646321	QC	<0.01	0.151	21.74	0.06	0.33	<0.01	<0.01	<0.01	0.12							
646327	Drill Core	<0.01	0.156	17.44	0.20	0.98	0.04	0.03	<0.01	0.11	0.051	0.085	0.008	0.17	0.59	0.21	N.A.
REP 646327	QC										0.053	0.088	0.008	0.17	0.60		
646335	Drill Core	<0.01	0.150	18.59	0.06	0.31	<0.01	<0.01	<0.01	1.72	0.115	0.247	0.025	0.72	0.51	2.64	N.A.
REP 646335	QC										0.115	0.245	0.024	0.65	0.51		
Core Reject Duplicates																	
646299	Drill Core	0.01	0.125	24.59	0.05	0.70	0.01	0.11	<0.01	0.05	0.005	0.077	0.005	0.34	1.36	0.04	N.A.
DUP 646299	QC	0.01	0.117	24.26	0.05	0.72	0.01	0.12	<0.01	0.05	0.005	0.077	0.005	0.33	1.32	0.05	N.A.
646333	Drill Core	<0.01	0.160	17.98	0.11	0.52	0.03	<0.01	<0.01	0.54	0.056	0.116	0.013	0.24	0.47	0.63	N.A.
DUP 646333	QC	<0.01	0.163	17.24	0.11	0.51	0.03	<0.01	<0.01	0.45	0.056	0.110	0.013	0.22	0.41	0.62	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard																4.22
STD CSC	Standard																4.23
STD CSC	Standard																4.28
STD CSC	Standard																4.13
STD FA10R	Standard																

QUALITY CONTROL REPORT

SMI08000606.2

		WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca
		kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01
STD FA10R	Standard		483	480	480																
STD FA10R	Standard		460	447	457																
STD OREAS76A	Standard																				
STD OREAS76A	Standard																				
STD OREAS76A	Standard																				
STD OREAS76A	Standard																				
STD R3NI	Standard																				
STD R3NI	Standard																				
STD R3T	Standard					0.077	0.829	1.98	4.15	198	0.538	0.062	0.09	32.67	<0.02	<0.01	0.024	0.04	<0.01	0.02	2.24
STD R3T	Standard					0.076	0.808	1.96	4.06	194	0.530	0.061	0.09	31.69	<0.02	<0.01	0.024	0.04	<0.01	0.02	2.20
STD R3T	Standard					0.074	0.824	2.05	4.15	195	0.533	0.061	0.09	32.60	<0.02	<0.01	0.023	0.04	<0.01	0.02	2.25
STD R3T	Standard					0.075	0.832	2.08	4.21	199	0.540	0.061	0.09	32.87	<0.02	<0.01	0.023	0.04	<0.01	0.02	2.27
STD FA10R Expected			485	472	476																
STD CDN-PGMS-14			259	119	451																
STD R3NI Expected																					
STD R3T Expected						0.077	0.805	1.98	4.1	190	0.525	0.061	0.09	34.17	0.04	0.01	0.024	0.04			2.23
STD CSC Expected																					
STD OREAS76A Expected																					
BLK	Blank																				
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank																				
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank																				
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank																				
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01

QUALITY CONTROL REPORT

SMI08000606.2

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
		P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard															16.19	
STD OREAS76A	Standard															17.28	
STD OREAS76A	Standard															17.57	
STD OREAS76A	Standard															18.06	
STD R3NI	Standard										0.775	0.414	0.053	5.01	0.12		
STD R3NI	Standard										0.762	0.410	0.050	5.59	0.15		
STD R3T	Standard	0.06	0.020	1.67	0.18	2.45	0.32	0.60	<0.01	15.53							
STD R3T	Standard	0.05	0.020	1.64	0.17	2.41	0.32	0.59	<0.01	14.82							
STD R3T	Standard	0.05	0.019	1.68	0.18	2.48	0.32	0.70	<0.01	15.53							
STD R3T	Standard	0.05	0.020	1.69	0.18	2.49	0.32	0.74	<0.01	15.43							
STD FA10R Expected																	
STD CDN-PGMS-14																	
STD R3NI Expected											0.42						
STD R3T Expected		0.05	0.02	1.64		2.44	0.31	0.59									
STD CSC Expected																4.19	
STD OREAS76A Expected																18	
BLK	Blank															<0.02	
BLK	Blank																
BLK	Blank																
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank																
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank																
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank																
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01							

QUALITY CONTROL REPORT

SMI08000606.2

		WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca
		kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
Prep Wash																					
G1	Prep Blank	<0.01	4	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.27	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.34
G1	Prep Blank	<0.01	5	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.43	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.39

QUALITY CONTROL REPORT

SMI08000606.2

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
		P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
BLK	Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01							
BLK	Blank																<0.02
BLK	Blank																<0.02
BLK	Blank																<0.02
Prep Wash																	
G1	Prep Blank	0.07	0.001	0.67	0.23	7.97	2.61	3.24	<0.01	<0.01	<0.001	<0.001	<0.001	0.07	0.03	0.02	N.A.
G1	Prep Blank	0.07	0.002	0.71	0.23	8.02	2.62	3.22	<0.01	<0.01	<0.001	<0.001	<0.001	0.08	0.05	<0.02	N.A.

Hole 08-253



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By:
 Receiving Lab: Canada-Smithers
 Received: July 10, 2008
 Report Date: August 19, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000607.2

CLIENT JOB INFORMATION

Project: Turnagain Ni
 Shipment ID: C08-253A
 P.O. Number
 Number of Samples: 44

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	40	Crush split and pulverize drill core to 200 mesh		
3B	42	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
7TD	44	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	44	Leached with H2O2 + NH4 citrate	1	Completed
2A (Total S)	44	Analysis by Leco	0.1	Completed
Specific Gravity	3	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS

Version 2 : G2A total S for all samples included.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain Ni
 Report Date: August 19, 2008

Page: 2 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000607.2

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646341	Drill Core	5.03	<2	5	5	<0.001	0.003	<0.02	<0.01	<2	0.176	0.012	0.15	8.80	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.30
646342	Drill Core	10.58	<2	<3	<2	<0.001	0.007	<0.02	<0.01	<2	0.155	0.011	0.15	8.35	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.54
646343	Drill Core	9.58	<2	9	5	<0.001	0.005	<0.02	<0.01	<2	0.147	0.011	0.15	8.88	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	3.06
646344	Drill Core	9.32	4	52	65	<0.001	0.021	<0.02	<0.01	<2	0.200	0.012	0.14	8.81	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	3.13
646345	Drill Core	11.15	<2	8	8	<0.001	0.006	<0.02	0.01	<2	0.161	0.011	0.17	10.04	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	2.21
646346	Drill Core	11.16	<2	5	6	<0.001	0.009	<0.02	0.01	<2	0.172	0.012	0.17	9.41	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.81
646347	Drill Core	10.36	<2	8	9	<0.001	0.011	<0.02	<0.01	<2	0.114	0.009	0.14	8.29	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.82
646348	Drill Core	11.05	<2	38	32	<0.001	0.080	<0.02	<0.01	<2	0.093	0.012	0.13	9.51	<0.02	0.01	<0.001	<0.01	<0.01	0.02	7.54
646349	Drill Core	12.32	<2	33	25	<0.001	0.082	<0.02	<0.01	<2	0.065	0.012	0.15	9.93	<0.02	<0.01	<0.001	<0.01	<0.01	0.03	11.16
646350	Rock Pulp	0.03	I.S.	I.S.	I.S.	<0.001	0.046	<0.02	<0.01	<2	0.385	0.026	0.11	12.35	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.09
646351	Rock Pulp	0.04	726	389	1447	<0.001	0.012	<0.02	<0.01	<2	0.086	0.003	0.08	4.80	<0.02	0.02	<0.001	<0.01	<0.01	0.01	3.52
646352	Drill Core	10.58	<2	10	12	<0.001	0.037	<0.02	0.01	<2	0.116	0.008	0.19	10.49	<0.02	<0.01	<0.001	<0.01	<0.01	0.03	4.42
646353	Drill Core	11.71	<2	<3	5	<0.001	0.081	<0.02	<0.01	<2	0.030	0.008	0.15	10.28	<0.02	<0.01	<0.001	<0.01	<0.01	0.05	10.14
646354	Drill Core	12.81	<2	4	8	<0.001	0.059	<0.02	<0.01	<2	0.014	0.009	0.15	12.39	<0.02	<0.01	<0.001	<0.01	<0.01	0.09	10.04
646355	Drill Core	12.01	<2	<3	6	<0.001	0.064	<0.02	<0.01	<2	0.015	0.012	0.13	10.36	<0.02	<0.01	<0.001	<0.01	<0.01	0.05	12.32
646356	Drill Core	11.28	5	8	10	0.001	0.086	<0.02	<0.01	<2	0.019	0.013	0.14	13.07	<0.02	<0.01	<0.001	<0.01	<0.01	0.07	11.33
646357	Drill Core	12.27	<2	10	6	<0.001	0.068	<0.02	<0.01	<2	0.025	0.012	0.13	9.19	<0.02	<0.01	<0.001	<0.01	<0.01	0.05	12.65
646358	Drill Core	11.17	2	9	14	<0.001	0.025	<0.02	<0.01	<2	0.070	0.010	0.16	9.70	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	7.02
646359	Drill Core	11.27	<2	9	12	<0.001	0.013	<0.02	<0.01	<2	0.093	0.012	0.17	10.37	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	4.74
646360	Drill Core	2.22	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	1.07	<0.02	0.08	<0.001	<0.01	<0.01	<0.01	2.05
646361	Drill Core	11.77	<2	9	13	<0.001	0.014	<0.02	<0.01	<2	0.079	0.011	0.15	9.75	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	5.38
646362	Drill Core	10.85	<2	21	20	<0.001	0.025	<0.02	<0.01	<2	0.096	0.012	0.15	9.59	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	5.39
646363	Drill Core	11.77	<2	20	22	<0.001	0.031	<0.02	<0.01	<2	0.088	0.011	0.13	8.31	<0.02	0.01	<0.001	<0.01	<0.01	0.01	7.70
646364	Drill Core	11.51	<2	18	17	<0.001	0.032	<0.02	<0.01	<2	0.118	0.013	0.14	9.15	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	5.30
646365	Drill Core	10.91	<2	14	14	<0.001	0.022	<0.02	<0.01	<2	0.087	0.011	0.12	7.40	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	7.30
646366	Drill Core	10.56	<2	13	14	<0.001	0.017	<0.02	<0.01	<2	0.087	0.011	0.14	7.94	<0.02	0.01	<0.001	<0.01	<0.01	0.01	5.45
646367	Drill Core	10.54	<2	13	13	<0.001	0.019	<0.02	<0.01	<2	0.087	0.012	0.13	7.82	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	4.86
646368	Drill Core	5.10	6	54	58	<0.001	0.010	<0.02	<0.01	<2	0.090	0.011	0.12	7.13	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	4.89
646369	Drill Core	5.52	<2	22	24	<0.001	0.097	<0.02	<0.01	<2	0.090	0.009	0.08	4.89	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	13.87
646370A	Drill Core	10.14	<2	40	62	<0.001	0.180	<0.02	<0.01	<2	0.128	0.019	0.09	7.34	<0.02	0.01	<0.001	<0.01	<0.01	0.02	12.21



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain Ni
 Report Date: August 19, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000607.2

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0	
646341	Drill Core	<0.01	0.158	20.91	0.07	0.31	0.02	0.01	<0.01	0.04	0.002	0.069	0.005	0.53	1.65	0.08	N.A.
646342	Drill Core	<0.01	0.176	20.62	0.08	0.37	0.03	0.01	<0.01	0.03	0.007	0.066	0.005	0.42	1.34	0.08	2.98
646343	Drill Core	<0.01	0.143	18.77	0.13	0.83	0.02	0.23	<0.01	0.10	0.004	0.101	0.006	0.40	1.05	0.15	N.A.
646344	Drill Core	<0.01	0.143	18.50	0.14	1.00	0.02	0.20	<0.01	0.22	0.018	0.151	0.007	0.60	1.25	0.32	N.A.
646345	Drill Core	0.01	0.151	20.24	0.16	0.73	0.05	0.12	<0.01	0.12	0.005	0.093	0.006	0.41	1.24	0.18	N.A.
646346	Drill Core	<0.01	0.166	22.18	0.05	0.20	<0.01	<0.01	<0.01	0.21	0.007	0.119	0.007	0.35	1.25	0.25	N.A.
646347	Drill Core	<0.01	0.131	17.02	0.06	0.25	0.01	0.01	<0.01	0.32	0.009	0.086	0.006	0.36	0.93	0.42	N.A.
646348	Drill Core	<0.01	0.136	13.48	0.14	0.49	0.04	0.02	<0.01	1.04	0.076	0.076	0.010	0.53	0.70	1.62	N.A.
646349	Drill Core	<0.01	0.135	13.45	0.19	0.65	0.07	0.01	<0.01	1.50	0.070	0.049	0.008	0.56	0.51	2.08	N.A.
646350	Rock Pulp	<0.01	0.171	19.47	0.02	0.27	0.03	0.09	<0.01	2.62	0.047	0.385	0.022	1.13	1.79	4.27	N.A.
646351	Rock Pulp	0.05	0.085	1.60	0.29	7.63	2.30	1.08	<0.01	0.24	0.008	0.011	<0.001	0.50	0.14	0.29	N.A.
646352	Drill Core	<0.01	0.135	15.23	0.08	0.31	0.03	0.01	<0.01	0.82	0.039	0.104	0.006	0.54	0.96	1.24	3.09
646353	Drill Core	<0.01	0.057	10.10	0.15	0.58	0.07	0.01	<0.01	1.97	0.082	0.029	0.008	1.35	0.68	3.15	N.A.
646354	Drill Core	<0.01	0.024	10.08	0.16	0.59	0.08	0.02	<0.01	2.70	0.056	0.012	0.008	1.78	0.79	4.21	N.A.
646355	Drill Core	<0.01	0.064	10.74	0.18	0.64	0.08	<0.01	<0.01	2.08	0.058	0.014	0.010	1.39	0.64	2.90	N.A.
646356	Drill Core	<0.01	0.049	10.49	0.14	0.38	0.08	<0.01	<0.01	2.79	0.083	0.017	0.011	1.53	0.54	4.20	N.A.
646357	Drill Core	<0.01	0.109	11.56	0.15	0.60	0.09	<0.01	<0.01	1.67	0.066	0.022	0.009	0.93	0.53	2.18	N.A.
646358	Drill Core	<0.01	0.134	17.80	0.09	0.43	0.05	<0.01	<0.01	0.53	0.022	0.050	0.006	0.40	0.89	0.60	N.A.
646359	Drill Core	<0.01	0.161	21.08	0.06	0.29	0.04	<0.01	<0.01	0.25	0.012	0.058	0.006	0.43	1.20	0.26	N.A.
646360	Drill Core	0.01	<0.001	0.22	0.07	8.18	3.60	1.21	<0.01	<0.01	<0.001	<0.001	<0.001	0.07	0.03	<0.02	N.A.
646361	Drill Core	<0.01	0.134	19.67	0.10	0.53	0.05	0.01	<0.01	0.27	0.013	0.052	0.006	0.37	1.01	0.28	N.A.
646362	Drill Core	<0.01	0.127	19.45	0.08	0.42	0.04	<0.01	<0.01	0.44	0.024	0.070	0.007	0.50	1.36	0.54	N.A.
646363	Drill Core	0.01	0.121	16.55	0.23	1.34	0.15	0.12	<0.01	0.36	0.031	0.071	0.007	0.38	0.78	0.40	N.A.
646364	Drill Core	<0.01	0.135	19.87	0.06	0.34	0.03	<0.01	<0.01	0.48	0.029	0.090	0.008	0.43	1.18	0.59	N.A.
646365	Drill Core	<0.01	0.181	19.04	0.08	0.39	0.05	<0.01	<0.01	0.27	0.021	0.061	0.006	0.35	1.05	0.35	N.A.
646366	Drill Core	0.03	0.132	18.52	0.12	1.05	0.03	0.12	<0.01	0.24	0.016	0.066	0.007	0.35	1.17	0.29	N.A.
646367	Drill Core	<0.01	0.153	20.77	0.06	0.32	0.03	<0.01	<0.01	0.25	0.017	0.064	0.007	0.32	1.10	0.28	N.A.
646368	Drill Core	<0.01	0.151	19.23	0.05	0.31	0.03	<0.01	<0.01	0.14	0.010	0.075	0.007	0.27	1.12	0.14	N.A.
646369	Drill Core	<0.01	0.236	11.10	0.12	0.58	0.11	<0.01	<0.01	0.71	0.091	0.094	0.008	0.54	0.45	0.96	N.A.
646370A	Drill Core	<0.01	0.190	11.03	0.13	0.95	0.10	0.01	<0.01	1.59	0.168	0.142	0.018	1.12	0.62	2.45	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain Ni
 Report Date: August 19, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000607.2

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646370B	Drill Core		2	35	49	<0.001	0.162	<0.02	<0.01	<2	0.115	0.017	0.09	6.82	<0.02	0.01	<0.001	<0.01	<0.01	0.02	11.89
646371	Drill Core	9.10	3	48	42	<0.001	0.043	<0.02	<0.01	<2	0.114	0.011	0.14	9.04	<0.02	0.01	<0.001	<0.01	<0.01	0.02	5.59
646372	Drill Core	10.32	<2	16	16	<0.001	0.047	<0.02	<0.01	<2	0.092	0.011	0.13	8.99	<0.02	0.02	<0.001	<0.01	<0.01	0.02	7.84
646373	Drill Core	8.68	<2	72	83	<0.001	0.044	<0.02	<0.01	<2	0.131	0.013	0.10	6.74	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	9.07
646374	Drill Core	8.57	<2	5	7	<0.001	0.010	<0.02	<0.01	<2	0.099	0.010	0.11	6.71	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	5.18
646375	Rock Pulp	<0.01	I.S.	I.S.	I.S.	<0.001	0.045	<0.02	<0.01	<2	0.395	0.026	0.12	13.13	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.13
646376	Rock Pulp	0.02	663	375	1422	0.001	0.012	<0.02	<0.01	<2	0.089	0.003	0.08	4.92	<0.02	0.02	<0.001	<0.01	<0.01	<0.01	3.75
646377	Drill Core	8.29	<2	7	7	<0.001	0.027	<0.02	<0.01	<2	0.050	0.010	0.09	5.70	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	7.63
646378	Drill Core	3.06	<2	<3	4	<0.001	0.052	<0.02	<0.01	<2	0.070	0.014	0.10	6.05	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	11.50
646379	Drill Core	6.56	4	35	49	<0.001	0.123	<0.02	<0.01	<2	0.156	0.025	0.14	11.55	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.96
646380	Drill Core	9.70	4	63	78	<0.001	0.140	<0.02	<0.01	<2	0.252	0.024	0.14	11.47	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.23
646381	Drill Core	10.19	4	42	59	<0.001	0.144	<0.02	<0.01	<2	0.287	0.028	0.14	12.19	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.75
646382	Drill Core	11.15	3	31	25	<0.001	0.075	<0.02	<0.01	<2	0.192	0.027	0.15	11.17	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.43
646383	Drill Core	10.82	5	73	101	<0.001	0.039	<0.02	<0.01	<2	0.239	0.015	0.15	9.96	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.76



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain Ni
 Report Date: August 19, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000607.2

Method		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
Analyte		P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG
Unit		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
646370B	Drill Core	<0.01	0.186	11.29	0.12	0.95	0.09	0.01	<0.01	1.42	0.152	0.124	0.016	0.92	0.46	2.14	N.A.
646371	Drill Core	0.06	0.179	14.74	0.51	2.80	0.07	1.13	<0.01	0.35	0.043	0.095	0.007	0.36	0.52	0.44	N.A.
646372	Drill Core	0.08	0.113	12.94	0.64	3.10	0.07	0.54	<0.01	0.47	0.047	0.084	0.008	0.46	0.52	0.57	3.02
646373	Drill Core	<0.01	0.205	14.80	0.11	1.15	0.07	0.01	<0.01	0.21	0.041	0.135	0.011	0.26	0.42	0.30	N.A.
646374	Drill Core	<0.01	0.197	20.05	0.07	0.44	0.03	<0.01	<0.01	0.11	0.010	0.079	0.007	0.19	0.81	0.13	N.A.
646375	Rock Pulp	<0.01	0.174	21.81	0.02	0.27	0.03	0.09	<0.01	2.71	0.046	0.402	0.025	1.19	1.79	4.26	N.A.
646376	Rock Pulp	0.05	0.089	1.67	0.32	8.36	2.43	1.19	<0.01	0.27	0.008	0.012	<0.001	0.44	0.14	0.28	N.A.
646377	Drill Core	<0.01	0.155	17.72	0.08	0.48	0.05	<0.01	<0.01	0.36	0.026	0.049	0.008	0.27	0.82	0.50	N.A.
646378	Drill Core	<0.01	0.232	13.18	0.13	0.66	0.08	<0.01	<0.01	0.36	0.051	0.075	0.012	0.29	0.66	0.47	N.A.
646379	Drill Core	<0.01	0.159	24.45	0.02	0.10	<0.01	<0.01	<0.01	1.13	0.122	0.154	0.020	0.78	1.58	1.37	N.A.
646380	Drill Core	<0.01	0.180	23.17	0.05	0.45	<0.01	<0.01	<0.01	1.13	0.136	0.246	0.020	0.83	1.51	1.55	N.A.
646381	Drill Core	<0.01	0.148	24.18	0.02	0.17	<0.01	<0.01	<0.01	1.49	0.135	0.253	0.022	1.10	1.89	2.13	N.A.
646382	Drill Core	<0.01	0.173	25.41	0.02	0.12	<0.01	<0.01	<0.01	0.95	0.069	0.154	0.019	0.61	1.45	1.20	N.A.
646383	Drill Core	<0.01	0.172	25.51	0.02	0.16	<0.01	<0.01	<0.01	0.31	0.039	0.149	0.008	0.56	1.67	0.37	N.A.

QUALITY CONTROL REPORT

SMI08000607.2

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
Pulp Duplicates																					
REP G1	QC																				
646345	Drill Core	11.15	<2	8	8	<0.001	0.006	<0.02	0.01	<2	0.161	0.011	0.17	10.04	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	2.21
REP 646345	QC					<0.001	0.006	<0.02	0.01	<2	0.157	0.011	0.17	9.85	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	2.21
646357	Drill Core	12.27	<2	10	6	<0.001	0.068	<0.02	<0.01	<2	0.025	0.012	0.13	9.19	<0.02	<0.01	<0.001	<0.01	<0.01	0.05	12.65
REP 646357	QC																				
646364	Drill Core	11.51	<2	18	17	<0.001	0.032	<0.02	<0.01	<2	0.118	0.013	0.14	9.15	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	5.30
REP 646364	QC																				
646368	Drill Core	5.10	6	54	58	<0.001	0.010	<0.02	<0.01	<2	0.090	0.011	0.12	7.13	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	4.89
REP 646368	QC																				
646379	Drill Core	6.56	4	35	49	<0.001	0.123	<0.02	<0.01	<2	0.156	0.025	0.14	11.55	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.96
REP 646379	QC					<0.001	0.118	<0.02	<0.01	<2	0.150	0.024	0.14	11.12	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.93
646381	Drill Core	10.19	4	42	59	<0.001	0.144	<0.02	<0.01	<2	0.287	0.028	0.14	12.19	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.75
REP 646381	QC		4	35	46																
Core Reject Duplicates																					
646354	Drill Core	12.81	<2	4	8	<0.001	0.059	<0.02	<0.01	<2	0.014	0.009	0.15	12.39	<0.02	<0.01	<0.001	<0.01	<0.01	0.09	10.04
DUP 646354	QC		<2	5	7	<0.001	0.058	<0.02	<0.01	<2	0.014	0.009	0.16	13.14	<0.02	<0.01	<0.001	<0.01	<0.01	0.09	10.37
Reference Materials																					
STD CDN-PGMS-14	Standard		251	120	417																
STD CDN-PGMS-14	Standard		212	96	421																
STD CDN-PGMS-14	Standard		223	115	414																
STD CDN-PGMS-14	Standard		275	102	406																
STD CSC	Standard																				
STD CSC	Standard																				
STD CSC	Standard																				
STD FA10R	Standard		459	450	457																
STD FA10R	Standard		445	441	440																
STD FA10R	Standard		484	472	487																
STD FA10R	Standard		460	447	457																

QUALITY CONTROL REPORT

SMI08000607.2

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0	
Pulp Duplicates																	
REP G1	QC																<0.02
646345	Drill Core	0.01	0.151	20.24	0.16	0.73	0.05	0.12	<0.01	0.12	0.005	0.093	0.006	0.41	1.24	0.18	N.A.
REP 646345	QC	0.01	0.142	20.03	0.15	0.71	0.05	0.12	<0.01	0.11							0.16
646357	Drill Core	<0.01	0.109	11.56	0.15	0.60	0.09	<0.01	<0.01	1.67	0.066	0.022	0.009	0.93	0.53	2.18	N.A.
REP 646357	QC																2.32
646364	Drill Core	<0.01	0.135	19.87	0.06	0.34	0.03	<0.01	<0.01	0.48	0.029	0.090	0.008	0.43	1.18	0.59	N.A.
REP 646364	QC										0.028	0.085	0.008	0.40	1.12		
646368	Drill Core	<0.01	0.151	19.23	0.05	0.31	0.03	<0.01	<0.01	0.14	0.010	0.075	0.007	0.27	1.12	0.14	N.A.
REP 646368	QC										0.010	0.073	0.007	0.25	1.00		
646379	Drill Core	<0.01	0.159	24.45	0.02	0.10	<0.01	<0.01	<0.01	1.13	0.122	0.154	0.020	0.78	1.58	1.37	N.A.
REP 646379	QC	<0.01	0.152	24.59	0.02	0.10	<0.01	<0.01	<0.01	1.10							
646381	Drill Core	<0.01	0.148	24.18	0.02	0.17	<0.01	<0.01	<0.01	1.49	0.135	0.253	0.022	1.10	1.89	2.13	N.A.
REP 646381	QC																
Core Reject Duplicates																	
646354	Drill Core	<0.01	0.024	10.08	0.16	0.59	0.08	0.02	<0.01	2.70	0.056	0.012	0.008	1.78	0.79	4.21	N.A.
DUP 646354	QC	<0.01	0.023	10.82	0.17	0.56	0.08	0.02	<0.01	2.68	0.053	0.012	0.007	1.48	0.67	3.97	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard																4.22
STD CSC	Standard																4.13
STD CSC	Standard																4.30
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																

QUALITY CONTROL REPORT

SMI08000607.2

		WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca
		kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01
STD OREAS76A	Standard																				
STD OREAS76A	Standard																				
STD OREAS76A	Standard																				
STD R3NI	Standard																				
STD R3NI	Standard																				
STD R3T	Standard					0.074	0.811	1.99	4.11	196	0.533	0.061	0.09	32.54	<0.02	<0.01	0.023	0.04	<0.01	0.02	2.22
STD R3T	Standard					0.074	0.806	1.99	4.14	196	0.534	0.061	0.09	32.59	<0.02	<0.01	0.023	0.04	<0.01	0.02	2.22
STD R3T	Standard					0.077	0.829	1.98	4.15	198	0.538	0.062	0.09	32.67	<0.02	<0.01	0.024	0.04	<0.01	0.02	2.24
STD R3T	Standard					0.076	0.808	1.96	4.06	194	0.530	0.061	0.09	31.69	<0.02	<0.01	0.024	0.04	<0.01	0.02	2.20
STD FA10R Expected			485	472	476																
STD CDN-PGMS-14			259	119	451																
STD R3NI Expected																					
STD R3T Expected						0.077	0.805	1.98	4.1	190	0.525	0.061	0.09	34.17	0.04	0.01	0.024	0.04			2.23
STD CSC Expected																					
STD OREAS76A Expected																					
BLK	Blank																				
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank																				

QUALITY CONTROL REPORT

SMI08000607.2

		WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca
		kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01
BLK	Blank																				
Prep Wash																					
G1	Prep Blank	<0.01	5	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.29	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.35
G1	Prep Blank	0.01	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.36	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.36
G1	Prep Blank																				

QUALITY CONTROL REPORT

SMI08000607.2

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
		P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
BLK	Blank																<0.02
Prep Wash																	
G1	Prep Blank	0.08	<0.001	0.63	0.22	8.10	2.72	1.41	<0.01	<0.01	<0.001	<0.001	<0.001	0.06	0.02	<0.02	N.A.
G1	Prep Blank	0.08	0.002	0.66	0.23	7.95	2.67	1.27	<0.01	<0.01	<0.001	<0.001	<0.001	0.05	0.02		N.A.
G1	Prep Blank																0.03



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By:
 Receiving Lab: Canada-Smithers
 Received: July 22, 2008
 Report Date: August 23, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000651.2

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-253B
 P.O. Number
 Number of Samples: 44

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	40	Crush split and pulverize drill core to 200 mesh		
3B	44	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
7TD	44	4 Acid digestion ICP-ES analysis.	0.5	Completed
8NiS	44	Leached with H2O2 + NH4 citrate	1	Completed
2A (TOTAL S)	44	Analysis by Leco	0.1	Completed
G8SG	2	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS

Version 2 : 8NiS & 2A(total S) for all samples included.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: August 23, 2008

Page: 2 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000651.2

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646384	Drill Core	11.89	<2	16	15	<0.001	0.006	<0.02	<0.01	<2	0.150	0.015	0.15	9.98	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.80
646385	Drill Core	12.52	<2	35	29	<0.001	0.007	<0.02	<0.01	<2	0.143	0.014	0.15	9.81	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.79
646386	Drill Core	11.07	<2	62	64	<0.001	0.011	<0.02	<0.01	<2	0.160	0.014	0.15	10.14	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.39
646387	Drill Core	12.11	3	71	116	<0.001	0.008	<0.02	<0.01	<2	0.143	0.013	0.15	9.64	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.30
646388	Drill Core	11.45	<2	53	62	<0.001	0.015	<0.02	<0.01	<2	0.119	0.012	0.13	8.79	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	4.75
646389	Drill Core	11.85	2	68	87	<0.001	0.026	<0.02	<0.01	<2	0.196	0.015	0.15	10.08	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.81
646390	Drill Core	1.76	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	3	0.002	<0.001	0.07	1.05	<0.02	0.08	<0.001	<0.01	<0.01	<0.01	1.84
646391	Drill Core	11.79	<2	11	10	<0.001	0.010	<0.02	<0.01	2	0.145	0.013	0.14	9.64	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.65
646392	Drill Core	11.63	<2	168	184	<0.001	0.007	<0.02	<0.01	<2	0.169	0.014	0.15	10.21	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.43
646393	Drill Core	10.64	<2	12	7	<0.001	0.003	<0.02	<0.01	<2	0.128	0.013	0.14	10.13	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.07
646394	Drill Core	10.40	<2	25	12	<0.001	0.003	<0.02	<0.01	<2	0.123	0.013	0.16	10.17	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.67
646395	Drill Core	10.25	<2	37	47	<0.001	0.008	<0.02	<0.01	<2	0.098	0.011	0.14	9.28	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.75
646396	Drill Core	9.97	<2	62	76	<0.001	0.011	<0.02	<0.01	<2	0.143	0.013	0.14	9.44	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.25
646397	Drill Core	9.94	<2	15	19	<0.001	0.006	<0.02	<0.01	<2	0.135	0.012	0.14	9.52	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.29
646398	Drill Core	12.63	3	80	125	<0.001	0.018	<0.02	<0.01	<2	0.141	0.013	0.15	9.49	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.54
646399	Drill Core	4.03	<2	16	15	<0.001	0.006	<0.02	<0.01	<2	0.118	0.013	0.13	9.56	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.70
646400	Rock Pulp	0.02	747	385	1462	<0.001	0.012	<0.02	<0.01	<2	0.088	0.003	0.08	4.89	<0.02	0.02	<0.001	<0.01	<0.01	<0.01	3.63
646401	Rock Pulp	0.05	<2	9	<2	<0.001	0.029	<0.02	<0.01	<2	0.253	0.016	0.11	8.70	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.70
646402	Drill Core	7.04	<2	18	20	<0.001	0.009	<0.02	<0.01	<2	0.046	0.006	0.10	4.97	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	12.58
646403	Drill Core	11.01	<2	<3	6	<0.001	0.010	<0.02	<0.01	<2	0.025	0.007	0.12	6.63	<0.02	<0.01	<0.001	<0.01	<0.01	0.03	11.65
646404	Drill Core	12.24	<2	<3	<2	<0.001	0.014	<0.02	<0.01	<2	0.005	0.006	0.14	6.75	<0.02	<0.01	<0.001	<0.01	<0.01	0.04	11.89
646405	Drill Core	9.03	<2	4	5	<0.001	0.027	<0.02	<0.01	<2	0.017	0.009	0.14	8.90	<0.02	<0.01	<0.001	<0.01	<0.01	0.05	10.95
646406	Drill Core	3.22	<2	<3	4	<0.001	0.015	<0.02	<0.01	<2	0.014	0.007	0.14	7.41	<0.02	<0.01	<0.001	<0.01	<0.01	0.05	11.86
646407	Drill Core	6.39	<2	<3	4	<0.001	0.018	<0.02	<0.01	<2	0.012	0.009	0.14	8.11	<0.02	<0.01	<0.001	<0.01	<0.01	0.06	12.24
646408	Drill Core	6.24	3	11	48	<0.001	0.075	<0.02	<0.01	<2	0.033	0.019	0.14	16.51	<0.02	<0.01	<0.001	<0.01	<0.01	0.05	8.50
646409	Drill Core	11.93	<2	<3	4	<0.001	0.015	<0.02	<0.01	<2	0.021	0.008	0.14	8.15	<0.02	<0.01	<0.001	<0.01	<0.01	0.05	11.58
646410	Drill Core	2.02	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	1.07	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	1.86
646411	Drill Core	6.45	<2	7	9	0.002	0.057	<0.02	<0.01	<2	0.022	0.019	0.15	16.88	<0.02	<0.01	<0.001	<0.01	<0.01	0.09	9.89
646412	Drill Core	6.66	<2	7	4	<0.001	0.011	<0.02	<0.01	<2	0.006	0.006	0.17	9.89	<0.02	<0.01	<0.001	<0.01	<0.01	0.09	10.94
646413	Drill Core	4.33	<2	4	13	0.002	0.055	<0.02	<0.01	<2	0.021	0.018	0.16	16.89	<0.02	<0.01	<0.001	<0.01	<0.01	0.08	8.67



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: August 23, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000651.2

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0	
646384	Drill Core	<0.01	0.144	24.04	0.03	0.30	<0.01	0.13	<0.01	0.12	0.005	0.080	0.008	0.82	3.10	0.08	N.A.
646385	Drill Core	<0.01	0.125	23.29	0.03	0.18	0.02	0.08	<0.01	0.13	0.008	0.068	0.006	0.32	1.22	0.11	N.A.
646386	Drill Core	<0.01	0.113	23.64	0.06	0.40	0.02	0.17	<0.01	0.14	0.011	0.095	0.008	0.82	2.94	0.12	N.A.
646387	Drill Core	<0.01	0.090	22.15	0.08	0.48	0.01	0.16	<0.01	0.14	0.008	0.077	0.007	0.82	2.91	0.11	N.A.
646388	Drill Core	<0.01	0.098	19.95	0.11	0.55	0.03	0.01	<0.01	0.24	0.016	0.068	0.007	0.69	2.31	0.20	N.A.
646389	Drill Core	<0.01	0.164	24.43	0.03	0.20	<0.01	<0.01	<0.01	0.15	0.026	0.092	0.007	0.91	3.21	0.14	N.A.
646390	Drill Core	<0.01	0.002	0.30	0.07	6.83	3.49	1.12	<0.01	0.02	<0.001	0.001	<0.001	0.08	0.07	<0.02	N.A.
646391	Drill Core	<0.01	0.158	22.58	0.07	0.40	0.01	<0.01	<0.01	0.22	0.010	0.076	0.007	0.70	2.56	0.18	N.A.
646392	Drill Core	<0.01	0.131	24.04	0.04	0.21	0.01	<0.01	<0.01	0.11	0.006	0.084	0.007	0.79	3.05	0.09	N.A.
646393	Drill Core	<0.01	0.159	23.62	0.06	0.33	<0.01	<0.01	<0.01	0.13	0.003	0.086	0.009	0.60	2.77	0.15	N.A.
646394	Drill Core	0.01	0.058	22.86	0.06	0.44	<0.01	<0.01	<0.01	0.10	0.003	0.088	0.010	0.43	2.23	0.11	N.A.
646395	Drill Core	0.03	0.077	19.61	0.15	0.82	0.01	0.01	<0.01	0.10	0.007	0.077	0.008	0.13	0.68	0.11	N.A.
646396	Drill Core	0.01	0.045	21.54	0.09	0.49	0.01	<0.01	<0.01	0.13	0.011	0.109	0.010	0.44	2.03	0.14	N.A.
646397	Drill Core	<0.01	0.113	21.67	0.09	0.53	0.01	<0.01	<0.01	0.10	0.006	0.099	0.009	0.50	2.20	0.12	N.A.
646398	Drill Core	<0.01	0.132	22.24	0.09	0.44	0.01	<0.01	<0.01	0.12	0.019	0.093	0.008	0.67	2.58	0.15	N.A.
646399	Drill Core	<0.01	0.160	21.70	0.06	0.34	<0.01	<0.01	<0.01	0.10	0.006	0.097	0.010	0.34	1.64	0.12	N.A.
646400	Rock Pulp	0.05	0.088	1.58	0.30	7.26	2.35	1.07	<0.01	0.27	0.009	0.012	<0.001	0.64	0.22	0.29	N.A.
646401	Rock Pulp	<0.01	0.147	24.59	0.02	0.32	<0.01	0.07	<0.01	1.02	0.030	0.218	0.012	0.85	2.48	1.28	N.A.
646402	Drill Core	<0.01	0.191	11.40	0.18	1.00	0.09	<0.01	<0.01	0.09	0.010	0.036	0.004	0.25	0.41	0.13	3.18
646403	Drill Core	0.02	0.113	10.74	0.22	1.58	0.09	0.01	<0.01	0.37	0.011	0.021	0.004	0.47	0.40	0.59	N.A.
646404	Drill Core	<0.01	0.095	11.05	0.16	0.77	0.12	0.01	<0.01	0.50	0.016	0.004	0.005	0.69	0.40	0.72	N.A.
646405	Drill Core	<0.01	0.081	11.26	0.15	0.62	0.09	<0.01	<0.01	1.21	0.029	0.012	0.005	0.57	0.33	1.73	N.A.
646406	Drill Core	<0.01	0.084	10.71	0.17	0.72	0.09	<0.01	<0.01	0.89	0.017	0.013	0.006	1.13	0.40	1.37	N.A.
646407	Drill Core	<0.01	0.083	10.40	0.18	0.92	0.10	<0.01	<0.01	0.76	0.019	0.010	0.007	0.94	0.32	1.23	N.A.
646408	Drill Core	<0.01	0.049	10.24	0.15	0.65	0.07	0.01	<0.01	3.73	0.082	0.026	0.015	4.44	0.41	6.42	N.A.
646409	Drill Core	0.04	0.083	9.82	0.37	2.09	0.09	<0.01	<0.01	0.84	0.017	0.013	0.006	0.86	0.31	1.33	N.A.
646410	Drill Core	0.01	<0.001	0.22	0.07	6.48	3.47	1.05	<0.01	0.03	0.001	0.001	<0.001	0.13	0.02	0.04	N.A.
646411	Drill Core	<0.01	0.030	8.48	0.32	1.40	0.09	0.02	<0.01	4.07	0.062	0.018	0.015	5.14	0.27	6.98	N.A.
646412	Drill Core	0.04	0.037	9.79	0.39	1.72	0.13	0.03	<0.01	0.97	0.012	0.004	0.004	0.99	0.26	1.57	3.13
646413	Drill Core	<0.01	0.028	9.34	0.28	1.23	0.14	0.04	<0.01	4.31	0.059	0.015	0.013	5.30	0.38	7.10	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: August 23, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000651.2

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646414	Drill Core	8.20	<2	<3	4	<0.001	0.031	<0.02	<0.01	<2	0.010	0.008	0.18	10.74	<0.02	<0.01	<0.001	<0.01	<0.01	0.08	10.84
646415	Drill Core	9.29	<2	4	11	0.002	0.074	<0.02	0.01	<2	0.024	0.010	0.23	14.31	<0.02	<0.01	<0.001	<0.01	<0.01	0.11	8.63
646416	Drill Core	2.93	<2	5	5	<0.001	0.021	<0.02	0.02	<2	0.133	0.006	0.22	10.00	<0.02	<0.01	<0.001	<0.01	<0.01	0.04	3.40
646417	Drill Core	10.82	18	25	20	<0.001	0.009	<0.02	0.02	<2	0.189	0.010	0.17	8.86	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	1.16
646418	Drill Core	9.30	<2	4	3	<0.001	0.023	<0.02	0.01	<2	0.138	0.013	0.10	7.96	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	1.38
646419	Drill Core	10.88	2	19	9	<0.001	0.070	<0.02	<0.01	<2	0.095	0.012	0.15	10.74	<0.02	0.01	<0.001	<0.01	<0.01	0.03	6.87
646420	Drill Core	10.58	<2	5	7	<0.001	0.016	<0.02	<0.01	<2	0.147	0.008	0.14	7.04	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	2.82
646421	Drill Core	10.28	<2	12	10	<0.001	0.026	<0.02	<0.01	<2	0.100	0.011	0.16	10.31	<0.02	0.02	<0.001	<0.01	<0.01	0.02	5.93
646422	Drill Core	10.36	<2	9	6	<0.001	0.018	<0.02	<0.01	<2	0.125	0.010	0.15	9.41	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	3.99
646423	Drill Core	10.26	<2	8	4	<0.001	0.013	<0.02	<0.01	<2	0.125	0.009	0.15	8.75	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	2.78
646424	Drill Core	10.36	4	11	16	<0.001	0.003	<0.02	<0.01	<2	0.202	0.008	0.12	5.40	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.69
646425	Rock Pulp	0.04	741	382	1400	<0.001	0.012	<0.02	<0.01	<2	0.090	0.003	0.08	4.93	<0.02	0.02	<0.001	<0.01	<0.01	<0.01	3.49
646426	Rock Pulp	0.02	I.S.	I.S.	I.S.	<0.001	0.029	<0.02	<0.01	<2	0.247	0.016	0.11	8.70	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.69
646427	Drill Core	4.25	<2	3	3	<0.001	0.004	<0.02	<0.01	<2	0.199	0.008	0.09	5.43	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	1.78



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: August 23, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000651.2

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S		SG
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%		
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02		0
646414	Drill Core	<0.01	0.035	9.83	0.27	1.24	0.16	0.03	<0.01	1.27	0.034	0.008	0.006	1.65	0.28	2.06	N.A.
646415	Drill Core	0.05	0.025	9.54	0.79	0.91	0.14	0.03	<0.01	2.56	0.074	0.010	0.003	1.10	0.21	4.35	N.A.
646416	Drill Core	<0.01	0.128	15.94	0.17	0.86	0.07	0.02	<0.01	1.03	0.023	0.119	0.005	1.48	0.77	1.52	N.A.
646417	Drill Core	<0.01	0.174	19.68	0.12	0.60	0.04	0.01	<0.01	0.48	0.010	0.162	0.008	0.81	1.54	0.58	N.A.
646418	Drill Core	<0.01	0.183	19.84	0.12	0.83	0.02	0.03	<0.01	0.73	0.024	0.134	0.012	0.93	1.75	0.94	N.A.
646419	Drill Core	0.02	0.104	12.14	0.27	1.83	0.06	0.02	<0.01	1.73	0.071	0.078	0.010	1.47	0.73	2.66	N.A.
646420	Drill Core	<0.01	0.151	17.56	0.20	1.26	0.08	0.04	<0.01	0.66	0.018	0.129	0.007	0.97	1.03	0.86	N.A.
646421	Drill Core	0.04	0.162	13.70	0.34	1.69	0.02	0.02	<0.01	0.85	0.029	0.091	0.009	1.05	0.85	1.18	N.A.
646422	Drill Core	<0.01	0.098	16.51	0.09	0.56	<0.01	<0.01	<0.01	0.69	0.019	0.113	0.009	0.87	1.21	0.91	N.A.
646423	Drill Core	0.01	0.100	17.81	0.31	1.31	<0.01	<0.01	<0.01	0.65	0.014	0.110	0.007	0.98	1.83	0.85	N.A.
646424	Drill Core	<0.01	0.031	20.32	0.18	1.13	<0.01	<0.01	<0.01	0.21	0.003	0.142	0.006	0.54	1.77	0.27	N.A.
646425	Rock Pulp	0.05	0.086	1.50	0.29	6.58	2.26	1.01	<0.01	0.27	0.009	0.013	<0.001	0.76	0.23	0.29	N.A.
646426	Rock Pulp	<0.01	0.146	23.99	0.02	0.32	<0.01	0.07	<0.01	1.00	0.029	0.220	0.013	1.24	4.02	1.40	N.A.
646427	Drill Core	<0.01	0.065	19.35	0.11	1.33	<0.01	0.01	<0.01	0.26	0.004	0.143	0.005	0.41	1.15	0.26	N.A.

QUALITY CONTROL REPORT

SMI08000651.2

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
Pulp Duplicates																					
646389	Drill Core	11.85	2	68	87	<0.001	0.026	<0.02	<0.01	<2	0.196	0.015	0.15	10.08	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.81
REP 646389	QC					<0.001	0.026	<0.02	<0.01	3	0.196	0.015	0.15	10.09	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.81
646390	Drill Core	1.76	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	3	0.002	<0.001	0.07	1.05	<0.02	0.08	<0.001	<0.01	<0.01	<0.01	1.84
REP 646390	QC																				
646404	Drill Core	12.24	<2	<3	<2	<0.001	0.014	<0.02	<0.01	<2	0.005	0.006	0.14	6.75	<0.02	<0.01	<0.001	<0.01	<0.01	0.04	11.89
REP 646404	QC																				
646408	Drill Core	6.24	3	11	48	<0.001	0.075	<0.02	<0.01	<2	0.033	0.019	0.14	16.51	<0.02	<0.01	<0.001	<0.01	<0.01	0.05	8.50
REP 646408	QC					<0.001	0.076	<0.02	<0.01	<2	0.033	0.020	0.14	16.65	<0.02	<0.01	<0.001	<0.01	<0.01	0.05	8.42
646409	Drill Core	11.93	<2	<3	4	<0.001	0.015	<0.02	<0.01	<2	0.021	0.008	0.14	8.15	<0.02	<0.01	<0.001	<0.01	<0.01	0.05	11.58
REP 646409	QC		3	<3	5																
646422	Drill Core	10.36	<2	9	6	<0.001	0.018	<0.02	<0.01	<2	0.125	0.010	0.15	9.41	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	3.99
REP 646422	QC																				
646423	Drill Core	10.26	<2	8	4	<0.001	0.013	<0.02	<0.01	<2	0.125	0.009	0.15	8.75	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	2.78
REP 646423	QC		<2	4	3																
Core Reject Duplicates																					
646410	Drill Core	2.02	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	1.07	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	1.86
DUP 646410	QC		<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	1.05	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	1.88
Reference Materials																					
STD CDN-PGMS-14	Standard		252	113	416																
STD CDN-PGMS-14	Standard		238	105	403																
STD CSC	Standard																				
STD CSC	Standard																				
STD CSC	Standard																				
STD CSC	Standard																				
STD FA10R	Standard		474	461	476																
STD FA10R	Standard		470	457	470																
STD OREAS76A	Standard																				
STD OREAS76A	Standard																				

QUALITY CONTROL REPORT

SMI08000651.2

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG	
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S		Cu	Ni	Co	Fe	Mg	TOT/S	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%		
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0	
Pulp Duplicates																		
646389	Drill Core	<0.01	0.164	24.43	0.03	0.20	<0.01	<0.01	<0.01	0.15	0.026	0.092	0.007	0.91	3.21	0.14	N.A.	
REP 646389	QC	<0.01	0.163	25.25	0.03	0.20	<0.01	<0.01	<0.01	0.15								
646390	Drill Core	<0.01	0.002	0.30	0.07	6.83	3.49	1.12	<0.01	0.02	<0.001	0.001	<0.001	0.08	0.07	<0.02	N.A.	
REP 646390	QC										<0.001	<0.001	<0.001	0.07	0.06			
646404	Drill Core	<0.01	0.095	11.05	0.16	0.77	0.12	0.01	<0.01	0.50	0.016	0.004	0.005	0.69	0.40	0.72	N.A.	
REP 646404	QC															0.71		
646408	Drill Core	<0.01	0.049	10.24	0.15	0.65	0.07	0.01	<0.01	3.73	0.082	0.026	0.015	4.44	0.41	6.42	N.A.	
REP 646408	QC	<0.01	0.050	10.16	0.15	0.66	0.07	<0.01	<0.01	3.62								
646409	Drill Core	0.04	0.083	9.82	0.37	2.09	0.09	<0.01	<0.01	0.84	0.017	0.013	0.006	0.86	0.31	1.33	N.A.	
REP 646409	QC										0.017	0.013	0.006	0.87	0.30			
646422	Drill Core	<0.01	0.098	16.51	0.09	0.56	<0.01	<0.01	<0.01	0.69	0.019	0.113	0.009	0.87	1.21	0.91	N.A.	
REP 646422	QC															0.93		
646423	Drill Core	0.01	0.100	17.81	0.31	1.31	<0.01	<0.01	<0.01	0.65	0.014	0.110	0.007	0.98	1.83	0.85	N.A.	
REP 646423	QC										0.014	0.104	0.007	0.92	1.73			
Core Reject Duplicates																		
646410	Drill Core	0.01	<0.001	0.22	0.07	6.48	3.47	1.05	<0.01	0.03	0.001	0.001	<0.001	0.13	0.02	0.04	N.A.	
DUP 646410	QC	0.01	<0.001	0.22	0.07	6.78	3.42	1.06	<0.01	<0.01	<0.001	<0.001	<0.001	0.10	0.02	<0.02	N.A.	
Reference Materials																		
STD CDN-PGMS-14	Standard																	
STD CDN-PGMS-14	Standard																	
STD CSC	Standard																4.17	
STD CSC	Standard																	4.30
STD CSC	Standard																	4.29
STD CSC	Standard																	4.31
STD FA10R	Standard																	
STD FA10R	Standard																	
STD OREAS76A	Standard																	17.60
STD OREAS76A	Standard																	16.84

QUALITY CONTROL REPORT

SMI08000651.2

		WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD		
		Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
		kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%	
		0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
STD OREAS76A	Standard																					
STD OREAS76A	Standard																					
STD R3NI	Standard																					
STD R3NI	Standard																					
STD R3NI	Standard																					
STD R3T	Standard					0.075	0.812	2.03	4.10	196	0.539	0.062	0.09	32.76	<0.02	<0.01	0.023	0.04	<0.01	0.02	2.22	
STD R3T	Standard					0.075	0.813	2.04	4.11	199	0.544	0.062	0.09	32.77	<0.02	<0.01	0.023	0.04	<0.01	0.02	2.22	
STD R3T	Standard					0.075	0.810	1.97	4.13	200	0.534	0.061	0.09	32.87	0.03	<0.01	0.024	0.03	<0.01	0.02	2.25	
STD R3T	Standard					0.076	0.806	1.99	4.10	197	0.534	0.061	0.09	32.88	0.03	<0.01	0.024	0.03	<0.01	0.02	2.25	
STD FA10R Expected			485	472	476																	
STD CDN-PGMS-14			259	119	451																	
STD R3T Expected						0.077	0.805	1.98	4.1	190	0.525	0.061	0.09	34.17	0.04	0.01	0.024	0.04			2.23	
STD CSC Expected																						
STD OREAS76A Expected																						
STD R3NI Expected																						
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
BLK	Blank																					
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
BLK	Blank																					
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	
BLK	Blank																					
BLK	Blank																					
BLK	Blank																					
BLK	Blank																					
BLK	Blank																					
Prep Wash																						

QUALITY CONTROL REPORT

SMI08000651.2

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
		P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
STD OREAS76A	Standard																16.80
STD OREAS76A	Standard																17.83
STD R3NI	Standard										0.788	0.420	0.054	5.78	0.16		
STD R3NI	Standard										0.445	0.430	0.058	10.32	0.18		
STD R3NI	Standard										0.375	0.444	0.061	10.95	0.18		
STD R3T	Standard	0.05	0.020	1.65	0.18	2.44	0.32	0.59	<0.01	15.49							
STD R3T	Standard	0.05	0.020	1.67	0.17	2.45	0.32	0.59	<0.01	15.37							
STD R3T	Standard	0.05	0.019	1.65	0.18	2.42	0.32	0.60	<0.01	17.12							
STD R3T	Standard	0.05	0.019	1.66	0.18	2.42	0.32	0.60	<0.01	17.08							
STD FA10R Expected																	
STD CDN-PGMS-14																	
STD R3T Expected		0.05	0.02	1.64		2.44	0.31	0.59									
STD CSC Expected																	4.19
STD OREAS76A Expected																	18
STD R3NI Expected												0.42					
BLK	Blank																
BLK	Blank																
BLK	Blank																<0.02
BLK	Blank																
BLK	Blank																<0.02
BLK	Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01							
BLK	Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01							
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank																<0.02
BLK	Blank																<0.02
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
Prep Wash																	

QUALITY CONTROL REPORT

SMI08000651.2

		WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca
		kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01
G1	Prep Blank	<0.01	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	2	<0.001	<0.001	0.07	2.22	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.28
G1	Prep Blank	<0.01	<2	<3	3	<0.001	<0.001	<0.02	<0.01	2	<0.001	<0.001	0.07	2.18	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.22

QUALITY CONTROL REPORT

SMI08000651.2

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A LECO	G8SG	
		P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
G1	Prep Blank	0.07	0.002	0.60	0.22	7.39	2.62	2.99	<0.01	0.02	<0.001	<0.001	<0.001	0.10	0.02	<0.02	N.A.
G1	Prep Blank	0.07	<0.001	0.59	0.22	7.12	2.61	2.86	<0.01	0.03	<0.001	<0.001	<0.001	0.11	0.01	<0.02	N.A.

Hole 08-254



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By:
 Receiving Lab: Canada-Smithers
 Received: July 22, 2008
 Report Date: August 27, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000652.2

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-254A
 P.O. Number
 Number of Samples: 48

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	46	Crush split and pulverize drill core to 200 mesh		
3B	46	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
7TD	48	4 Acid digestion ICP-ES analysis.	0.5	Completed
8NiS	48	Leached with H2O2 + NH4 citrate	1	Completed
2A (TOTAL S)	48	Analysis by Leco	0.1	Completed
G8SG	3	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS

Version 2 : G2A & 8NiS data for all samples included.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: August 27, 2008

Page: 2 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000652.2

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646428	Drill Core	14.90	<2	5	6	<0.001	0.026	<0.02	<0.01	<2	0.111	0.011	0.12	8.48	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	7.89
646429	Drill Core	11.87	<2	9	10	<0.001	0.014	<0.02	<0.01	<2	0.211	0.013	0.14	10.08	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	2.74
646430A	Drill Core	12.06	<2	6	7	<0.001	0.019	<0.02	<0.01	<2	0.129	0.011	0.13	9.42	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	4.61
646430B	Drill Core		3	5	7	<0.001	0.020	<0.02	<0.01	<2	0.134	0.012	0.13	9.49	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	4.83
646431	Drill Core	12.06	<2	9	10	<0.001	0.016	<0.02	0.01	<2	0.158	0.014	0.16	10.44	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	2.19
646432	Drill Core	11.55	3	5	8	<0.001	0.017	<0.02	<0.01	<2	0.189	0.012	0.12	8.94	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.91
646433	Drill Core	12.15	2	15	15	<0.001	0.021	<0.02	<0.01	<2	0.216	0.014	0.15	9.24	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.92
646434	Drill Core	11.67	4	11	12	<0.001	0.020	<0.02	<0.01	<2	0.177	0.012	0.12	7.90	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.37
646435	Drill Core	12.94	5	25	55	<0.001	0.024	<0.02	0.01	<2	0.392	0.027	0.15	11.30	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.85
646436	Drill Core	11.44	4	12	15	<0.001	0.017	<0.02	<0.01	<2	0.163	0.011	0.12	9.04	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.95
646437	Drill Core	11.05	<2	12	12	<0.001	0.012	<0.02	<0.01	<2	0.112	0.009	0.15	8.00	<0.02	0.03	<0.001	<0.01	<0.01	0.01	5.48
646438	Drill Core	11.51	2	14	14	<0.001	0.025	<0.02	<0.01	<2	0.156	0.010	0.12	7.05	<0.02	0.02	<0.001	<0.01	<0.01	<0.01	3.56
646439	Drill Core	11.26	4	35	43	<0.001	0.038	<0.02	<0.01	<2	0.246	0.013	0.13	7.74	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.41
646440	Drill Core	2.54	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	0.001	<0.001	0.07	1.17	<0.02	0.08	<0.001	<0.01	<0.01	<0.01	2.01
646441	Drill Core	11.35	5	36	43	<0.001	0.035	<0.02	<0.01	<2	0.291	0.015	0.13	8.64	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.67
646442	Drill Core	10.83	3	13	15	<0.001	0.015	<0.02	<0.01	<2	0.224	0.013	0.14	8.35	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.02
646443	Drill Core	11.57	3	12	20	<0.001	0.010	<0.02	<0.01	<2	0.199	0.013	0.14	8.51	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.62
646444	Drill Core	11.89	9	14	18	<0.001	0.015	<0.02	<0.01	<2	0.212	0.014	0.14	8.56	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.58
646445	Drill Core	11.95	3	55	54	<0.001	0.018	<0.02	<0.01	<2	0.227	0.015	0.13	8.25	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.72
646446	Drill Core	11.75	10	4	7	<0.001	0.005	<0.02	<0.01	<2	0.200	0.014	0.12	7.80	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.98
646447	Drill Core	11.14	<2	5	10	<0.001	0.002	<0.02	<0.01	<2	0.191	0.013	0.13	8.09	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.03
646448	Drill Core	11.07	<2	4	7	<0.001	0.003	<0.02	<0.01	<2	0.198	0.014	0.14	8.53	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.79
646449	Drill Core	11.85	<2	3	6	<0.001	0.002	<0.02	<0.01	<2	0.205	0.013	0.14	8.42	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.68
646450	Rock Pulp	0.02	I.S.	I.S.	I.S.	<0.001	0.097	<0.02	<0.01	3	0.327	0.015	0.05	8.96	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	3.12
646451	Rock Pulp	<0.01	I.S.	I.S.	I.S.	<0.001	0.031	<0.02	<0.01	<2	0.245	0.017	0.11	8.82	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.71
646452	Drill Core	12.09	<2	13	14	<0.001	0.004	<0.02	<0.01	<2	0.214	0.013	0.14	8.41	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.31
646453	Drill Core	10.69	<2	14	18	<0.001	0.016	<0.02	<0.01	<2	0.214	0.013	0.14	8.89	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.14
646454	Drill Core	11.94	6	7	9	<0.001	0.013	<0.02	<0.01	<2	0.208	0.013	0.13	8.44	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.64
646455	Drill Core	11.97	<2	13	19	<0.001	0.027	<0.02	0.01	<2	0.253	0.015	0.14	9.32	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.79
646456	Drill Core	11.73	<2	9	15	<0.001	0.019	<0.02	<0.01	<2	0.201	0.013	0.13	8.50	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.45



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: August 27, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000652.2

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0	
646428	Drill Core	<0.01	0.168	16.03	0.08	0.40	0.07	0.01	<0.01	1.04	0.027	0.086	0.010	1.29	2.06	1.16	N.A.
646429	Drill Core	<0.01	0.132	21.30	0.03	0.14	0.03	<0.01	<0.01	0.83	0.016	0.152	0.010	1.44	3.11	0.99	N.A.
646430A	Drill Core	<0.01	0.190	19.31	0.05	0.25	0.04	<0.01	<0.01	0.85	0.020	0.107	0.010	1.48	3.40	0.99	N.A.
646430B	Drill Core	<0.01	0.193	19.29	0.05	0.26	0.05	<0.01	<0.01	0.90	0.022	0.110	0.010	1.46	3.18	1.05	N.A.
646431	Drill Core	<0.01	0.291	21.97	0.03	0.18	0.02	<0.01	<0.01	0.64	0.016	0.127	0.010	1.30	3.26	0.74	N.A.
646432	Drill Core	<0.01	0.226	22.17	0.03	0.17	0.02	<0.01	<0.01	0.44	0.016	0.124	0.008	1.05	3.43	0.50	3.22
646433	Drill Core	<0.01	0.256	22.43	0.03	0.14	0.02	<0.01	<0.01	0.55	0.022	0.156	0.009	1.32	3.58	0.62	N.A.
646434	Drill Core	<0.01	0.170	21.97	0.02	0.14	0.02	<0.01	<0.01	0.33	0.019	0.108	0.008	1.06	4.08	0.36	N.A.
646435	Drill Core	<0.01	0.191	19.77	0.04	0.18	0.04	<0.01	<0.01	1.40	0.024	0.370	0.022	0.80	0.94	1.71	N.A.
646436	Drill Core	<0.01	0.160	20.42	0.03	0.18	0.03	<0.01	<0.01	0.56	0.017	0.131	0.009	1.04	3.16	0.62	N.A.
646437	Drill Core	0.03	0.121	15.87	0.15	2.29	0.05	0.63	<0.01	0.34	0.013	0.092	0.007	0.81	2.14	0.41	N.A.
646438	Drill Core	0.03	0.171	15.03	0.10	2.65	0.08	1.53	<0.01	0.57	0.027	0.128	0.009	0.63	0.96	0.65	N.A.
646439	Drill Core	0.01	0.154	21.13	0.03	0.70	<0.01	0.02	<0.01	0.38	0.039	0.183	0.009	0.86	2.45	0.43	N.A.
646440	Drill Core	0.02	0.002	0.30	0.07	7.80	3.61	1.15	<0.01	<0.01	<0.001	<0.001	<0.001	0.13	0.04	<0.02	N.A.
646441	Drill Core	<0.01	0.285	24.09	0.01	0.10	0.01	<0.01	<0.01	0.22	0.036	0.157	0.007	1.06	3.29	0.25	N.A.
646442	Drill Core	<0.01	0.180	24.06	0.02	0.12	0.02	<0.01	<0.01	0.14	0.015	0.112	0.007	1.50	5.17	0.17	N.A.
646443	Drill Core	<0.01	0.189	24.33	0.01	0.08	<0.01	<0.01	<0.01	0.07	0.011	0.071	0.005	1.31	4.42	0.09	N.A.
646444	Drill Core	<0.01	0.196	24.66	0.01	0.08	<0.01	<0.01	<0.01	0.10	0.016	0.082	0.005	1.44	4.72	0.12	N.A.
646445	Drill Core	<0.01	0.302	24.63	0.01	0.11	0.01	<0.01	<0.01	0.13	0.017	0.067	0.003	0.56	1.63	0.13	N.A.
646446	Drill Core	<0.01	0.223	24.29	0.01	0.11	0.01	<0.01	<0.01	0.06	0.005	0.077	0.005	1.41	5.29	0.08	N.A.
646447	Drill Core	<0.01	0.290	24.38	0.02	0.14	0.01	<0.01	<0.01	0.02	0.002	0.055	0.004	1.24	4.19	0.04	N.A.
646448	Drill Core	<0.01	0.389	23.47	0.03	0.18	0.02	<0.01	<0.01	0.04	0.003	0.078	0.006	1.45	4.90	0.07	N.A.
646449	Drill Core	<0.01	0.158	23.35	0.03	0.18	0.02	0.02	<0.01	0.05	0.002	0.075	0.005	1.34	4.58	0.08	N.A.
646450	Rock Pulp	<0.01	0.412	14.14	0.14	2.86	0.23	0.05	<0.01	0.89	0.095	0.261	0.013	1.26	1.73	1.04	N.A.
646451	Rock Pulp	<0.01	0.160	22.91	0.02	0.32	<0.01	0.07	<0.01	1.17	0.031	0.222	0.014	1.35	4.24	1.42	N.A.
646452	Drill Core	<0.01	0.192	24.07	0.02	0.13	0.02	<0.01	<0.01	0.08	0.004	0.085	0.005	1.57	5.36	0.10	3.24
646453	Drill Core	<0.01	0.186	23.93	0.02	0.13	0.01	0.01	<0.01	0.20	0.016	0.109	0.006	1.26	3.88	0.23	N.A.
646454	Drill Core	<0.01	0.178	23.82	0.03	0.26	0.02	0.07	<0.01	0.12	0.013	0.084	0.005	1.45	4.68	0.15	N.A.
646455	Drill Core	0.01	0.227	23.38	0.03	0.19	0.02	0.01	<0.01	0.49	0.025	0.166	0.007	0.70	1.48	0.52	N.A.
646456	Drill Core	<0.01	0.213	22.51	0.04	0.29	0.03	0.07	<0.01	0.40	0.018	0.129	0.007	1.56	4.56	0.44	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: August 27, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000652.2

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646457	Drill Core	11.06	<2	19	27	<0.001	0.013	<0.02	<0.01	<2	0.222	0.014	0.13	8.08	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.86
646458	Drill Core	12.06	<2	6	5	<0.001	0.004	<0.02	<0.01	<2	0.195	0.012	0.12	7.46	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.07
646459	Drill Core	11.35	<2	7	15	<0.001	0.008	<0.02	<0.01	<2	0.235	0.013	0.12	7.75	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.77
646460A	Drill Core	11.59	7	15	16	<0.001	0.003	<0.02	<0.01	<2	0.207	0.012	0.13	7.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.18
646460B	Drill Core		<2	7	9	<0.001	0.004	<0.02	<0.01	<2	0.198	0.011	0.12	7.46	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.12
646461	Drill Core	11.61	<2	16	15	<0.001	0.009	<0.02	<0.01	<2	0.207	0.013	0.12	7.39	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.38
646462	Drill Core	10.95	<2	<3	12	<0.001	0.001	<0.02	<0.01	<2	0.221	0.012	0.11	6.67	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.56
646463	Drill Core	11.77	3	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	0.230	0.012	0.11	6.88	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.61
646464	Drill Core	12.26	2	3	6	<0.001	<0.001	<0.02	<0.01	<2	0.223	0.012	0.12	7.24	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.80
646465	Drill Core	11.71	24	175	70	<0.001	0.001	<0.02	<0.01	<2	0.247	0.012	0.12	7.25	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.20
646466	Drill Core	11.84	<2	<3	5	<0.001	<0.001	<0.02	<0.01	2	0.234	0.011	0.10	6.43	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.02
646467	Drill Core	11.94	<2	4	<2	<0.001	<0.001	<0.02	<0.01	<2	0.268	0.011	0.11	6.46	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.48
646468	Drill Core	10.79	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	0.259	0.010	0.10	5.66	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.12
646469	Drill Core	11.43	7	11	9	<0.001	<0.001	<0.02	<0.01	<2	0.241	0.011	0.11	7.00	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.30
646470	Drill Core	2.44	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	0.002	<0.001	0.07	1.09	<0.02	0.08	<0.001	<0.01	<0.01	<0.01	2.01
646471	Drill Core	10.77	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	0.261	0.011	0.10	6.33	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.69
646472	Drill Core	10.71	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	0.276	0.011	0.10	5.27	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.69
646473	Drill Core	11.75	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	0.262	0.010	0.09	5.41	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.05



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: August 27, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000652.2

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0	
646457	Drill Core	<0.01	0.196	23.16	0.04	0.20	0.02	<0.01	<0.01	0.30	0.013	0.139	0.008	1.24	4.20	0.33	N.A.
646458	Drill Core	<0.01	0.140	23.24	0.04	0.35	0.02	0.06	<0.01	0.11	0.004	0.099	0.006	1.32	4.78	0.13	N.A.
646459	Drill Core	<0.01	0.174	23.30	0.04	0.29	0.02	0.03	<0.01	0.14	0.007	0.126	0.006	0.95	3.71	0.17	N.A.
646460A	Drill Core	<0.01	0.195	26.48	0.03	0.19	0.02	<0.01	<0.01	0.08	0.004	0.090	0.005	1.28	4.67	0.09	N.A.
646460B	Drill Core	<0.01	0.183	25.12	0.03	0.19	0.02	<0.01	<0.01	0.08	0.004	0.091	0.005	1.24	4.54	0.10	N.A.
646461	Drill Core	<0.01	0.208	26.64	0.02	0.15	0.02	<0.01	<0.01	0.08	0.010	0.085	0.005	1.09	4.02	0.10	N.A.
646462	Drill Core	<0.01	0.264	26.93	0.02	0.17	<0.01	<0.01	<0.01	0.04	0.002	0.067	0.004	1.00	4.33	0.05	N.A.
646463	Drill Core	<0.01	0.291	27.43	0.02	0.16	<0.01	<0.01	<0.01	0.02	0.001	0.053	0.003	0.93	3.77	0.03	N.A.
646464	Drill Core	<0.01	0.279	26.40	0.02	0.14	<0.01	<0.01	<0.01	0.03	<0.001	0.064	0.004	1.08	4.22	0.04	N.A.
646465	Drill Core	<0.01	0.319	27.30	0.03	0.26	0.01	0.06	<0.01	0.03	0.002	0.057	0.003	0.49	1.74	0.05	N.A.
646466	Drill Core	<0.01	0.267	25.69	0.03	0.27	<0.01	0.08	<0.01	0.06	0.001	0.102	0.005	0.99	4.44	0.08	N.A.
646467	Drill Core	<0.01	0.338	28.11	0.02	0.19	<0.01	0.04	<0.01	0.04	0.001	0.080	0.004	0.87	3.88	0.06	N.A.
646468	Drill Core	<0.01	0.283	26.42	0.04	0.36	0.01	0.10	<0.01	0.06	0.001	0.104	0.005	1.01	4.75	0.07	N.A.
646469	Drill Core	<0.01	0.211	25.62	0.06	0.45	0.01	0.12	<0.01	0.09	0.001	0.120	0.006	0.86	3.58	0.10	N.A.
646470	Drill Core	0.01	0.002	0.39	0.07	8.12	3.60	1.15	<0.01	<0.01	<0.001	0.002	<0.001	0.10	0.14	0.03	N.A.
646471	Drill Core	<0.01	0.257	26.74	0.03	0.29	<0.01	0.03	<0.01	0.10	<0.001	0.134	0.006	0.94	4.71	0.09	N.A.
646472	Drill Core	<0.01	0.123	27.83	0.03	0.27	<0.01	0.03	<0.01	0.10	<0.001	0.132	0.005	0.58	3.23	0.11	3.10
646473	Drill Core	<0.01	0.147	26.53	0.03	0.19	0.01	0.03	<0.01	0.06	<0.001	0.082	0.003	0.48	2.09	0.06	N.A.

QUALITY CONTROL REPORT

SMI08000652.2

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca
Unit	kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01
Pulp Duplicates																				
REP G1	QC				<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.37	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.33
646431	Drill Core	12.06	<2	9	10	<0.001	0.016	<0.02	0.01	<2	0.158	0.014	0.16	10.44	<0.02	<0.01	<0.001	<0.01	<0.01	2.19
REP 646431	QC																			
646434	Drill Core	11.67	4	11	12	<0.001	0.020	<0.02	<0.01	<2	0.177	0.012	0.12	7.90	<0.02	<0.01	<0.001	<0.01	<0.01	2.37
REP 646434	QC																			
646444	Drill Core	11.89	9	14	18	<0.001	0.015	<0.02	<0.01	<2	0.212	0.014	0.14	8.56	<0.02	<0.01	<0.001	<0.01	<0.01	0.58
REP 646444	QC																			
646463	Drill Core	11.77	3	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	0.230	0.012	0.11	6.88	<0.02	<0.01	<0.001	<0.01	<0.01	0.61
REP 646463	QC				<0.001	<0.001	<0.02	<0.01	<2	0.229	0.012	0.11	6.77	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.59
646467	Drill Core	11.94	<2	4	<2	<0.001	<0.001	<0.02	<0.01	<2	0.268	0.011	0.11	6.46	<0.02	<0.01	<0.001	<0.01	<0.01	0.48
REP 646467	QC																			
646472	Drill Core	10.71	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	0.276	0.011	0.10	5.27	<0.02	<0.01	<0.001	<0.01	<0.01	0.69
REP 646472	QC		<2	3	<2															
Core Reject Duplicates																				
646458	Drill Core	12.06	<2	6	5	<0.001	0.004	<0.02	<0.01	<2	0.195	0.012	0.12	7.46	<0.02	<0.01	<0.001	<0.01	<0.01	2.07
DUP 646458	QC		<2	<3	5	<0.001	0.004	<0.02	<0.01	<2	0.193	0.011	0.12	7.42	<0.02	<0.01	<0.001	<0.01	<0.01	2.05
Reference Materials																				
STD CDN-PGMS-14	Standard		238	105	403															
STD CDN-PGMS-14	Standard		270	102	385															
STD CSC	Standard																			
STD CSC	Standard																			
STD CSC	Standard																			
STD CSC	Standard																			
STD FA10R	Standard		470	457	470															
STD FA10R	Standard		469	452	461															
STD FA10R	Standard		478	458	476															
STD FA10R	Standard		430	434	430															
STD OREAS76A	Standard																			

QUALITY CONTROL REPORT

SMI08000652.2

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S		Cu	Ni	Co	Fe	Mg	TOT/S	SG
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
Pulp Duplicates																	
REP G1	QC	0.07	0.001	0.66	0.23	7.86	2.63	3.08	<0.01	<0.01							
646431	Drill Core	<0.01	0.291	21.97	0.03	0.18	0.02	<0.01	<0.01	0.64	0.016	0.127	0.010	1.30	3.26	0.74	N.A.
REP 646431	QC										0.016	0.129	0.010	1.29	3.29		
646434	Drill Core	<0.01	0.170	21.97	0.02	0.14	0.02	<0.01	<0.01	0.33	0.019	0.108	0.008	1.06	4.08	0.36	N.A.
REP 646434	QC															0.38	
646444	Drill Core	<0.01	0.196	24.66	0.01	0.08	<0.01	<0.01	<0.01	0.10	0.016	0.082	0.005	1.44	4.72	0.12	N.A.
REP 646444	QC										0.016	0.083	0.006	1.46	4.84		
646463	Drill Core	<0.01	0.291	27.43	0.02	0.16	<0.01	<0.01	<0.01	0.02	0.001	0.053	0.003	0.93	3.77	0.03	N.A.
REP 646463	QC	<0.01	0.307	27.73	0.02	0.15	<0.01	0.01	<0.01	0.02							
646467	Drill Core	<0.01	0.338	28.11	0.02	0.19	<0.01	0.04	<0.01	0.04	0.001	0.080	0.004	0.87	3.88	0.06	N.A.
REP 646467	QC															0.05	
646472	Drill Core	<0.01	0.123	27.83	0.03	0.27	<0.01	0.03	<0.01	0.10	<0.001	0.132	0.005	0.58	3.23	0.11	3.10
REP 646472	QC										<0.001	0.132	0.005	0.60	3.28		
Core Reject Duplicates																	
646458	Drill Core	<0.01	0.140	23.24	0.04	0.35	0.02	0.06	<0.01	0.11	0.004	0.099	0.006	1.32	4.78	0.13	N.A.
DUP 646458	QC	<0.01	0.139	22.61	0.05	0.36	0.02	0.06	<0.01	0.10	0.003	0.096	0.006	1.32	4.75	0.13	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard																4.17
STD CSC	Standard																4.30
STD CSC	Standard																4.31
STD CSC	Standard																4.30
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																17.60

QUALITY CONTROL REPORT

SMI08000652.2

		WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD		
		Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
		kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%	
		0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
STD OREAS76A	Standard																					
STD OREAS76A	Standard																					
STD OREAS76A	Standard																					
STD R3NI	Standard																					
STD R3NI	Standard																					
STD R3NI	Standard																					
STD R3NI	Standard																					
STD R3NI	Standard																					
STD R3NI	Standard																					
STD R3T	Standard					0.078	0.811	1.96	4.10	197	0.534	0.062	0.09	32.44	0.03	<0.01	0.024	0.04	<0.01	0.02	2.19	
STD R3T	Standard					0.077	0.807	1.96	4.15	198	0.537	0.062	0.09	32.53	0.03	<0.01	0.024	0.03	<0.01	0.02	2.20	
STD R3T	Standard					0.075	0.816	2.03	4.14	196	0.535	0.061	0.09	32.66	<0.02	<0.01	0.024	0.04	<0.01	0.02	2.25	
STD R3T	Standard					0.075	0.820	2.01	4.09	197	0.530	0.060	0.09	32.39	<0.02	<0.01	0.024	0.04	<0.01	0.02	2.25	
STD CDN-PGMS-14			259	119	451																	
STD R3T Expected						0.077	0.805	1.98	4.1	190	0.525	0.061	0.09	34.17	0.04	0.01	0.024	0.04			2.23	
STD FA10R Expected			485	472	476																	
STD CSC Expected																						
STD OREAS76A Expected																						
STD R3NI Expected																						
BLK	Blank																					
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
BLK	Blank																					

QUALITY CONTROL REPORT

SMI08000652.2

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
		P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
STD OREAS76A	Standard																18.21
STD OREAS76A	Standard																17.92
STD OREAS76A	Standard																17.64
STD R3NI	Standard										0.811	0.417	0.053	5.14	0.17		
STD R3NI	Standard										0.788	0.420	0.054	5.78	0.16		
STD R3NI	Standard										0.522	0.454	0.063	11.48	0.20		
STD R3NI	Standard										0.522	0.454	0.063	11.48	0.20		
STD R3NI	Standard										0.566	0.449	0.062	11.18	0.20		
STD R3NI	Standard										0.507	0.446	0.055	6.18	0.62		
STD R3T	Standard	0.05	0.020	1.65	0.17	2.41	0.32	0.59	<0.01	16.35							
STD R3T	Standard	0.05	0.020	1.65	0.17	2.41	0.32	0.59	<0.01	16.15							
STD R3T	Standard	0.03	0.020	1.67	0.17	2.43	0.32	0.58	<0.01	16.80							
STD R3T	Standard	0.04	0.019	1.65	0.17	2.41	0.32	0.58	<0.01	16.61							
STD CDN-PGMS-14																	
STD R3T Expected		0.05	0.02	1.64		2.44	0.31	0.59									
STD FA10R Expected																	
STD CSC Expected																	4.19
STD OREAS76A Expected																	18
STD R3NI Expected												0.42					
BLK	Blank																<0.02
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01							
BLK	Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01							
BLK	Blank																
BLK	Blank																
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		

QUALITY CONTROL REPORT

SMI08000652.2

		WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca
		kg	ppb	ppb	ppb	%	%	%	%	GM/T	%	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.22	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.35
G1	Prep Blank	<0.01	<2	<3	<2																
G1	Prep Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.33	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.31

QUALITY CONTROL REPORT

SMI08000652.2

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS2A	LECO	G8SG
		P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank															<0.02	
BLK	Blank															<0.02	
BLK	Blank															<0.02	
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
Prep Wash																	
G1	Prep Blank	0.07	<0.001	0.64	0.23	7.83	2.74	3.00	<0.01	0.04	<0.001	<0.001	<0.001	0.12	0.04	0.03	N.A.
G1	Prep Blank										<0.001	<0.001	<0.001	0.11	0.04	<0.02	N.A.
G1	Prep Blank	0.08	<0.001	0.66	0.23	7.76	2.63	3.05	<0.01	<0.01							



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Email Distribution List
 Receiving Lab: Canada-Smithers
 Received: July 31, 2008
 Report Date: September 25, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000677.1

CLIENT JOB INFORMATION

Project: Turnagain Ni
 Shipment ID: C08-254B
 P.O. Number
 Number of Samples: 41

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	37	Crush split and pulverize drill core to 200 mesh		
3B	41	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
7TD	41	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	41	Leached with H2O2 + NH4 citrate	1	Completed
2A (Total S)	41	Analysis by Leco	0.1	Completed
Specific Gravity	3	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS

Revised to include 2A-total S for all samples

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC: Email Distribution List



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain Ni

Report Date: September 25, 2008

Page: 2 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000677.1

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646474	Drill Core	10.15	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	0.260	0.011	0.10	5.75	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.19
646475	Rock Pulp	0.01	I.S.	I.S.	I.S.	<0.001	0.055	<0.02	0.03	<2	0.224	0.011	0.11	8.68	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	4.16
646476	Rock Pulp	<0.01	I.S.	I.S.	I.S.	0.001	0.047	<0.02	<0.01	<2	0.398	0.027	0.12	12.77	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.16
646477	Drill Core	10.57	<2	9	6	<0.001	<0.001	<0.02	<0.01	<2	0.254	0.011	0.11	5.87	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.22
646478	Drill Core	11.66	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	0.246	0.011	0.09	5.39	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.92
646479	Drill Core	10.55	<2	4	3	<0.001	0.003	<0.02	<0.01	<2	0.283	0.012	0.10	6.21	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.52
646480	Drill Core	9.49	<2	6	11	<0.001	<0.001	<0.02	<0.01	<2	0.243	0.011	0.10	5.79	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.32
646481	Drill Core	10.16	<2	4	3	<0.001	<0.001	<0.02	<0.01	<2	0.258	0.011	0.09	5.36	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.36
646482	Drill Core	10.36	<2	9	11	<0.001	0.002	<0.02	<0.01	<2	0.284	0.012	0.10	5.82	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.78
646483	Drill Core	9.44	6	17	7	<0.001	0.021	<0.02	<0.01	<2	0.244	0.014	0.11	7.46	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.53
646484	Drill Core	9.97	<2	5	4	<0.001	0.026	<0.02	<0.01	<2	0.112	0.015	0.11	8.79	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	5.57
646485	Drill Core	9.16	<2	5	4	<0.001	0.020	<0.02	<0.01	<2	0.092	0.014	0.12	9.67	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	5.43
646486	Drill Core	9.17	<2	27	22	<0.001	0.061	<0.02	<0.01	<2	0.098	0.019	0.13	13.08	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	5.33
646487	Drill Core	11.83	<2	82	46	<0.001	0.033	<0.02	<0.01	<2	0.195	0.014	0.12	8.99	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	2.98
646488	Drill Core	10.64	<2	33	35	<0.001	0.070	<0.02	<0.01	<2	0.259	0.023	0.12	10.12	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.18
646489	Drill Core	11.90	6	48	45	<0.001	0.092	<0.02	<0.01	<2	0.299	0.017	0.12	8.38	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.21
646490A	Drill Core	10.46	8	54	51	<0.001	0.083	<0.02	<0.01	<2	0.319	0.016	0.12	7.79	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.84
646490B	Drill Core		10	62	49	<0.001	0.084	<0.02	<0.01	<2	0.326	0.016	0.12	8.00	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.85
646491	Drill Core	9.94	<2	81	74	<0.001	0.032	<0.02	0.02	<2	0.256	0.013	0.13	7.44	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.01
646492	Drill Core	8.39	<2	35	36	<0.001	0.072	<0.02	<0.01	<2	0.218	0.013	0.11	7.23	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.89
646493	Drill Core	9.50	<2	64	63	<0.001	0.056	<0.02	<0.01	<2	0.228	0.013	0.11	6.71	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.91
646494	Drill Core	9.46	<2	64	55	<0.001	0.010	<0.02	<0.01	<2	0.202	0.012	0.11	6.72	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.62
646495	Drill Core	11.02	<2	96	107	<0.001	0.013	<0.02	<0.01	<2	0.211	0.012	0.11	6.80	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.64
646496	Drill Core	10.63	<2	115	136	<0.001	0.084	<0.02	<0.01	<2	0.270	0.015	0.11	7.38	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.66
646497	Drill Core	10.59	3	81	102	<0.001	0.063	<0.02	<0.01	<2	0.331	0.020	0.11	8.17	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.42
646498	Drill Core	11.57	5	72	91	<0.001	0.088	<0.02	<0.01	<2	0.450	0.022	0.11	8.32	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.41
646499	Drill Core	10.98	3	26	35	<0.001	0.060	<0.02	<0.01	<2	0.336	0.026	0.11	9.36	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.20
646500	Rock Pulp	0.02	I.S.	I.S.	I.S.	<0.001	0.031	<0.02	<0.01	<2	0.244	0.016	0.12	8.84	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.70
646501	Rock Pulp	0.03	I.S.	I.S.	I.S.	<0.001	0.055	<0.02	0.02	<2	0.223	0.011	0.11	8.82	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	4.25
646502	Drill Core	10.95	<2	10	16	<0.001	0.029	<0.02	<0.01	<2	0.255	0.018	0.11	7.75	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.23



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain Ni

Report Date: September 25, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000677.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS 2A	G8SG	
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%		
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0	
646474	Drill Core	<0.01	0.172	25.14	<0.01	0.28	0.02	0.23	<0.01	0.10	<0.001	0.077	0.003	0.42	1.89	0.08	N.A.
646475	Rock Pulp	<0.01	1.029	12.78	<0.01	3.80	0.30	0.28	<0.01	0.55	0.055	0.174	0.006	0.31	0.30	0.48	N.A.
646476	Rock Pulp	<0.01	0.187	20.39	<0.01	0.30	0.03	0.28	<0.01	3.25	0.049	0.399	0.023	1.09	1.66	4.12	N.A.
646477	Drill Core	<0.01	0.253	25.74	<0.01	0.20	0.01	0.19	<0.01	0.07	<0.001	0.051	0.003	0.36	1.55	0.06	N.A.
646478	Drill Core	<0.01	0.229	26.20	<0.01	0.26	<0.01	0.10	<0.01	0.09	<0.001	0.072	0.003	0.35	1.85	0.08	N.A.
646479	Drill Core	<0.01	0.283	25.67	<0.01	0.27	<0.01	0.08	<0.01	0.12	0.003	0.102	0.005	0.34	1.75	0.12	N.A.
646480	Drill Core	<0.01	0.291	24.78	<0.01	0.32	<0.01	0.23	<0.01	0.15	0.001	0.116	0.005	0.36	2.06	0.15	N.A.
646481	Drill Core	<0.01	0.526	25.45	<0.01	0.29	<0.01	0.16	<0.01	0.14	0.001	0.111	0.004	0.34	1.77	0.12	N.A.
646482	Drill Core	<0.01	0.234	26.03	<0.01	0.26	<0.01	0.24	<0.01	0.10	0.002	0.101	0.004	0.35	1.42	0.10	3.18
646483	Drill Core	<0.01	0.181	23.07	<0.01	0.53	0.01	0.20	<0.01	0.98	0.022	0.129	0.009	0.48	1.31	1.14	N.A.
646484	Drill Core	<0.01	0.136	15.97	<0.01	0.93	0.04	0.34	<0.01	1.42	0.024	0.110	0.013	0.50	0.85	1.69	N.A.
646485	Drill Core	<0.01	0.125	16.27	<0.01	0.60	0.04	0.43	<0.01	1.58	0.018	0.087	0.012	0.45	0.92	1.89	N.A.
646486	Drill Core	<0.01	0.183	14.03	<0.01	0.55	0.02	0.24	<0.01	3.04	0.060	0.105	0.019	0.82	0.66	4.09	N.A.
646487	Drill Core	<0.01	0.126	21.11	<0.01	0.19	0.01	<0.01	<0.01	1.46	0.032	0.146	0.010	0.70	1.27	1.63	N.A.
646488	Drill Core	<0.01	0.105	23.97	<0.01	0.10	<0.01	<0.01	<0.01	1.61	0.074	0.225	0.017	0.94	1.52	1.93	N.A.
646489	Drill Core	<0.01	0.164	25.14	<0.01	0.12	0.01	<0.01	<0.01	0.94	0.099	0.249	0.010	0.98	1.82	1.03	N.A.
646490A	Drill Core	<0.01	0.306	24.58	<0.01	0.18	<0.01	0.02	<0.01	0.61	0.083	0.252	0.010	0.73	1.66	0.62	N.A.
646490B	Drill Core	<0.01	0.306	25.00	<0.01	0.18	<0.01	0.01	<0.01	0.64	0.083	0.253	0.010	0.78	1.90	0.60	N.A.
646491	Drill Core	<0.01	0.333	24.40	<0.01	0.20	0.02	<0.01	<0.01	0.34	0.030	0.177	0.007	0.53	1.92	0.28	N.A.
646492	Drill Core	<0.01	0.218	24.04	<0.01	0.21	<0.01	0.02	<0.01	0.42	0.071	0.164	0.008	0.63	2.36	0.38	3.09
646493	Drill Core	<0.01	0.221	25.18	<0.01	0.16	0.01	0.02	<0.01	0.33	0.055	0.128	0.006	0.69	2.61	0.29	N.A.
646494	Drill Core	<0.01	0.209	25.33	<0.01	0.10	<0.01	<0.01	<0.01	0.13	0.010	0.066	0.004	0.49	2.20	0.11	N.A.
646495	Drill Core	<0.01	0.164	25.67	<0.01	0.09	0.01	<0.01	<0.01	0.15	0.013	0.078	0.004	0.55	2.41	0.13	N.A.
646496	Drill Core	<0.01	0.186	24.78	<0.01	0.09	<0.01	<0.01	<0.01	0.70	0.086	0.201	0.008	0.89	2.23	0.71	N.A.
646497	Drill Core	<0.01	0.143	24.93	<0.01	0.08	<0.01	<0.01	<0.01	1.00	0.065	0.294	0.014	1.00	2.41	1.08	N.A.
646498	Drill Core	<0.01	0.107	25.14	<0.01	0.06	<0.01	<0.01	<0.01	1.40	0.087	0.412	0.017	1.16	2.17	1.49	N.A.
646499	Drill Core	<0.01	0.121	25.36	<0.01	0.06	<0.01	0.08	<0.01	1.31	0.062	0.317	0.020	1.01	2.13	1.43	N.A.
646500	Rock Pulp	<0.01	0.159	23.36	<0.01	0.31	<0.01	0.17	<0.01	1.24	0.030	0.225	0.012	0.81	2.30	1.34	N.A.
646501	Rock Pulp	<0.01	1.044	12.98	<0.01	3.89	0.30	0.24	<0.01	0.54	0.059	0.184	0.007	0.36	0.38	0.48	N.A.
646502	Drill Core	<0.01	0.105	25.44	<0.01	0.06	<0.01	0.02	<0.01	0.72	0.027	0.208	0.012	0.69	2.05	0.85	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain Ni

Report Date: September 25, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000677.1

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646503	Drill Core	10.61	<2	10	15	<0.001	0.015	<0.02	<0.01	<2	0.213	0.014	0.11	6.68	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.21
646504	Drill Core	11.39	5	25	28	<0.001	0.017	<0.02	<0.01	<2	0.225	0.013	0.11	7.10	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.76
646505	Drill Core	11.21	4	104	114	<0.001	0.059	<0.02	<0.01	<2	0.321	0.016	0.11	7.67	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.08
646506	Drill Core	11.92	5	54	64	<0.001	0.094	<0.02	<0.01	<2	0.400	0.021	0.11	9.19	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.16
646507	Drill Core	11.30	5	14	17	<0.001	0.054	<0.02	<0.01	<2	0.220	0.017	0.11	7.52	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.76
646508	Drill Core	10.89	5	32	40	<0.001	0.061	<0.02	<0.01	<2	0.285	0.017	0.11	7.66	<0.02	0.03	<0.001	<0.01	<0.01	<0.01	1.57
646509	Drill Core	11.15	6	68	67	<0.001	0.029	<0.02	0.01	<2	0.275	0.014	0.11	6.82	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.40
646510	Drill Core	11.23	4	74	80	<0.001	0.061	<0.02	<0.01	<2	0.346	0.015	0.10	6.99	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.20
646511	Drill Core	10.43	2	31	36	<0.001	0.030	<0.02	<0.01	<2	0.264	0.012	0.11	6.12	<0.02	0.02	<0.001	<0.01	<0.01	<0.01	1.72
646512	Drill Core	10.37	11	17	24	<0.001	0.033	<0.02	<0.01	<2	0.338	0.015	0.10	7.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.38
646513	Drill Core	6.42	7	49	58	<0.001	0.045	<0.02	<0.01	<2	0.322	0.015	0.10	7.22	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.71



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain Ni

Report Date: September 25, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000677.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS 2A Leco	G8SG	
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%		
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0	
646503	Drill Core	<0.01	0.133	26.11	<0.01	0.07	<0.01	0.36	<0.01	0.29	0.015	0.114	0.006	0.63	2.41	0.27	N.A.
646504	Drill Core	<0.01	0.204	25.06	<0.01	0.08	<0.01	<0.01	<0.01	0.22	0.016	0.106	0.005	0.55	2.25	0.20	N.A.
646505	Drill Core	<0.01	0.219	25.15	<0.01	0.05	<0.01	<0.01	<0.01	0.58	0.062	0.249	0.010	0.79	2.62	0.58	N.A.
646506	Drill Core	<0.01	0.277	25.92	<0.01	0.07	<0.01	<0.01	<0.01	1.64	0.095	0.347	0.014	1.06	2.03	1.59	N.A.
646507	Drill Core	<0.01	0.183	24.40	<0.01	0.32	<0.01	<0.01	<0.01	0.70	0.054	0.186	0.012	0.83	2.83	0.71	N.A.
646508	Drill Core	0.02	0.253	22.87	<0.01	1.19	<0.01	0.11	<0.01	0.77	0.065	0.246	0.012	0.79	2.10	0.79	N.A.
646509	Drill Core	<0.01	0.241	25.22	<0.01	0.10	<0.01	<0.01	<0.01	0.32	0.027	0.169	0.007	0.63	2.98	0.24	N.A.
646510	Drill Core	<0.01	0.288	25.07	<0.01	0.05	<0.01	<0.01	<0.01	0.52	0.064	0.272	0.010	0.95	3.19	0.50	N.A.
646511	Drill Core	0.03	0.136	16.61	<0.01	2.39	0.79	0.70	<0.01	0.69	0.032	0.250	0.009	0.53	0.74	0.72	N.A.
646512	Drill Core	<0.01	0.159	24.37	<0.01	0.24	<0.01	0.02	<0.01	0.65	0.033	0.311	0.011	0.72	1.64	0.67	3.19
646513	Drill Core	0.02	0.132	21.90	<0.01	0.91	0.39	0.13	<0.01	0.79	0.047	0.304	0.012	0.83	1.69	0.87	N.A.

QUALITY CONTROL REPORT

SMI08000677.1

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
Pulp Duplicates																					
646483	Drill Core	9.44	6	17	7	<0.001	0.021	<0.02	<0.01	<2	0.244	0.014	0.11	7.46	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.53
REP 646483	QC																				
646491	Drill Core	9.94	<2	81	74	<0.001	0.032	<0.02	0.02	<2	0.256	0.013	0.13	7.44	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.01
REP 646491	QC																				
646496	Drill Core	10.63	<2	115	136	<0.001	0.084	<0.02	<0.01	<2	0.270	0.015	0.11	7.38	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.66
REP 646496	QC					<0.001	0.086	<0.02	<0.01	<2	0.273	0.015	0.11	7.46	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.67
646501	Rock Pulp	0.03	I.S.	I.S.	I.S.	<0.001	0.055	<0.02	0.02	<2	0.223	0.011	0.11	8.82	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	4.25
REP 646501	QC																				
646505	Drill Core	11.21	4	104	114	<0.001	0.059	<0.02	<0.01	<2	0.321	0.016	0.11	7.67	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.08
REP 646505	QC																				
Core Reject Duplicates																					
646488	Drill Core	10.64	<2	33	35	<0.001	0.070	<0.02	<0.01	<2	0.259	0.023	0.12	10.12	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.18
DUP 646488	QC		<2	31	32	<0.001	0.072	<0.02	<0.01	<2	0.260	0.023	0.12	10.33	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.12
Reference Materials																					
STD CDN-PGMS-14	Standard		327	120	418																
STD CDN-PGMS-14	Standard		261	113	419																
STD CDN-PGMS-14	Standard		284	103	415																
STD CDN-PGMS-14	Standard		241	113	416																
STD CSC	Standard																				
STD CSC	Standard																				
STD CSC	Standard																				
STD FA10R	Standard		473	466	473																
STD FA10R	Standard		477	462	475																
STD FA10R	Standard		469	459	469																
STD FA10R	Standard		456	444	454																
STD OREAS76A	Standard																				
STD OREAS76A	Standard																				
STD OREAS76A	Standard																				

QUALITY CONTROL REPORT

SMI08000677.1

Method		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS 2A Leco	G8SG	
Analyte		P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG
Unit		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
Pulp Duplicates																	
646483	Drill Core	<0.01	0.181	23.07	<0.01	0.53	0.01	0.20	<0.01	0.98	0.022	0.129	0.009	0.48	1.31	1.14	N.A.
REP 646483	QC										0.021	0.127	0.009	0.45	1.24		
646491	Drill Core	<0.01	0.333	24.40	<0.01	0.20	0.02	<0.01	<0.01	0.34	0.030	0.177	0.007	0.53	1.92	0.28	N.A.
REP 646491	QC															0.27	
646496	Drill Core	<0.01	0.186	24.78	<0.01	0.09	<0.01	<0.01	<0.01	0.70	0.086	0.201	0.008	0.89	2.23	0.71	N.A.
REP 646496	QC	<0.01	0.200	24.88	<0.01	0.09	<0.01	<0.01	<0.01	0.71							
646501	Rock Pulp	<0.01	1.044	12.98	<0.01	3.89	0.30	0.24	<0.01	0.54	0.059	0.184	0.007	0.36	0.38	0.48	N.A.
REP 646501	QC										0.059	0.187	0.007	0.37	0.38		
646505	Drill Core	<0.01	0.219	25.15	<0.01	0.05	<0.01	<0.01	<0.01	0.58	0.062	0.249	0.010	0.79	2.62	0.58	N.A.
REP 646505	QC										0.059	0.241	0.010	0.76	2.50		
Core Reject Duplicates																	
646488	Drill Core	<0.01	0.105	23.97	<0.01	0.10	<0.01	<0.01	<0.01	1.61	0.074	0.225	0.017	0.94	1.52	1.93	N.A.
DUP 646488	QC	<0.01	0.104	24.14	<0.01	0.10	<0.01	<0.01	<0.01	1.68	0.077	0.226	0.017	0.95	1.58	1.87	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard																4.29
STD CSC	Standard																4.34
STD CSC	Standard																4.37
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																17.41
STD OREAS76A	Standard																17.06
STD OREAS76A	Standard																16.88

QUALITY CONTROL REPORT

SMI08000677.1

		WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca
		kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01
STD R3NI	Standard																				
STD R3NI	Standard																				
STD R3T	Standard					0.077	0.800	2.02	4.17	200	0.542	0.064	0.09	32.65	0.03	<0.01	0.024	0.04	<0.01	0.02	2.26
STD R3T	Standard					0.077	0.805	2.02	4.16	207	0.542	0.063	0.09	32.70	0.03	<0.01	0.024	0.04	<0.01	0.02	2.25
STD R3T	Standard					0.077	0.800	2.01	4.14	199	0.542	0.063	0.09	32.82	0.03	<0.01	0.024	0.04	<0.01	0.02	2.25
STD R3T	Standard					0.078	0.815	2.02	4.18	213	0.544	0.064	0.09	33.14	0.03	<0.01	0.025	0.04	<0.01	0.02	2.28
STD R3NI Expected																					
STD R3T Expected						0.077	0.805	1.98	4.1	190	0.525	0.061	0.09	34.17	0.04	0.01	0.024	0.04			2.23
STD FA10R Expected			485	472	476																
STD CDN-PGMS-14			259	119	451																
STD CSC Expected																					
STD OREAS76A Expected																					
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.29	<0.02	0.06	<0.001	<0.01	<0.01	<0.01	2.25

QUALITY CONTROL REPORT

SMI08000677.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS 2A Leco	G8SG	
		P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
STD R3NI	Standard										0.811	0.417	0.053	5.14	0.17		
STD R3NI	Standard										0.757	0.399	0.050	5.00	0.16		
STD R3T	Standard	0.07	0.021	1.69	<0.01	2.39	0.33	0.71	<0.01	17.08							
STD R3T	Standard	0.06	0.021	1.69	<0.01	2.40	0.33	0.60	<0.01	17.82							
STD R3T	Standard	0.06	0.021	1.69	<0.01	2.40	0.33	0.59	<0.01	17.27							
STD R3T	Standard	0.06	0.021	1.69	<0.01	2.42	0.33	0.60	<0.01	17.60							
STD R3NI Expected											0.42						
STD R3T Expected		0.05	0.02	1.64		2.44	0.31	0.59									
STD FA10R Expected																	
STD CDN-PGMS-14																	
STD CSC Expected																	4.19
STD OREAS76A Expected																	18
BLK	Blank																<0.02
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank																
BLK	Blank																
BLK	Blank	<0.01	<0.001	0.08	<0.01	<0.01	<0.01	0.30	<0.01	<0.01							
BLK	Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01							
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																<0.02
BLK	Blank																<0.02
Prep Wash																	
G1	Prep Blank	0.08	<0.001	0.63	<0.01	7.38	2.34	3.03	<0.01	0.14	<0.001	<0.001	<0.001	0.09	0.04	<0.02	N.A.

QUALITY CONTROL REPORT

SMI08000677.1

		WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca
		kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01
G1	Prep Blank	<0.01	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.30	<0.02	0.06	<0.001	<0.01	<0.01	<0.01	2.27

QUALITY CONTROL REPORT

SMI08000677.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS 2A Leco	G8SG	
		P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
G1	Prep Blank	0.08	<0.001	0.65	<0.01	7.58	2.34	2.89	<0.01	0.03	<0.001	<0.001	<0.001	0.08	0.04	<0.02	N.A.

Hole 08-255



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Email Distribution List
 Receiving Lab: Canada-Smithers
 Received: August 05, 2008
 Report Date: September 26, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000689.2

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-255A
 P.O. Number
 Number of Samples: 50

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	45	Crush split and pulverize drill core to 200 mesh		
3B	49	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	49	Analysis by Leco	0.1	Completed
7TD	49	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	49	Leached with H2O2 + NH4 citrate	1	Completed
Specific Gravity	3	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS

Ver.2 to include 2A-total S

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC: Email Distribution List



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 26, 2008

Page: 2 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000689.2

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646514	Drill Core	12.67	<2	8	7	0.26	<0.001	0.015	<0.02	<0.01	<2	0.200	0.012	0.14	8.41	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646515	Drill Core	11.77	<2	9	7	0.37	<0.001	0.008	<0.02	<0.01	<2	0.211	0.012	0.14	8.88	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646516	Drill Core	12.01	<2	6	6	0.12	<0.001	0.003	<0.02	<0.01	<2	0.229	0.011	0.14	8.10	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646517	Drill Core	12.35	<2	8	12	0.23	<0.001	0.005	<0.02	<0.01	<2	0.221	0.012	0.14	8.63	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646518	Drill Core	11.72	<2	7	7	0.19	<0.001	0.004	<0.02	<0.01	<2	0.199	0.012	0.14	7.76	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646519	Drill Core	11.26	<2	9	10	0.51	<0.001	0.011	<0.02	<0.01	<2	0.158	0.013	0.13	8.43	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646520A	Drill Core	10.10	3	30	23	0.27	<0.001	0.005	<0.02	<0.01	<2	0.197	0.012	0.13	8.27	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646520B	Drill Core		<2	22	21	0.25	<0.001	0.006	<0.02	<0.01	<2	0.192	0.012	0.13	8.51	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646521	Drill Core	12.11	<2	7	5	0.19	<0.001	0.005	<0.02	0.01	<2	0.203	0.013	0.14	8.70	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646522	Drill Core	10.68	<2	3	4	0.33	<0.001	0.008	<0.02	<0.01	<2	0.171	0.012	0.14	8.64	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646523	Drill Core	10.68	<2	13	13	0.51	<0.001	0.010	<0.02	<0.01	<2	0.155	0.010	0.12	7.47	<0.02	0.02	<0.001	<0.01	<0.01	<0.01
646524	Drill Core	11.36	<2	17	8	0.46	<0.001	0.014	<0.02	<0.01	<2	0.067	0.008	0.12	5.97	<0.02	0.03	<0.001	<0.01	<0.01	0.01
646525	Rock Pulp	0.04	I.S.	I.S.	I.S.	0.97	<0.001	0.091	<0.02	<0.01	<2	0.338	0.016	0.05	9.04	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646526	Rock Pulp	0.03	I.S.	I.S.	I.S.	4.18	0.001	0.047	<0.02	<0.01	<2	0.390	0.027	0.12	12.67	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646527	Drill Core	12.04	<2	13	10	1.26	<0.001	0.033	<0.02	<0.01	<2	0.130	0.015	0.13	8.11	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646528	Drill Core	11.59	<2	<3	2	0.73	<0.001	0.021	<0.02	<0.01	<2	0.112	0.015	0.14	8.51	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646529	Drill Core	12.73	<2	7	3	0.67	<0.001	0.019	<0.02	<0.01	<2	0.086	0.014	0.13	7.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646530	Drill Core	2.10	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.001	<0.001	0.07	1.13	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
646531	Drill Core	12.33	<2	12	22	1.05	<0.001	0.042	<0.02	<0.01	<2	0.126	0.016	0.12	7.87	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646532	Drill Core	11.35	<2	38	47	0.36	<0.001	0.015	<0.02	<0.01	<2	0.155	0.012	0.12	7.25	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646533	Drill Core	11.11	3	31	43	0.13	<0.001	0.018	<0.02	0.02	<2	0.207	0.014	0.14	8.18	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646534	Drill Core	12.29	<2	18	24	0.07	<0.001	0.007	<0.02	<0.01	<2	0.181	0.014	0.14	8.26	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646535	Drill Core	11.59	<2	<3	4	0.09	<0.001	0.002	<0.02	<0.01	<2	0.197	0.013	0.14	8.36	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646536	Drill Core	10.64	<2	23	26	0.11	<0.001	0.003	<0.02	<0.01	<2	0.204	0.013	0.13	7.83	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646537	Drill Core	11.90	<2	13	16	0.06	<0.001	0.002	<0.02	<0.01	<2	0.204	0.013	0.14	8.36	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646538	Drill Core	10.66	<2	11	14	0.13	<0.001	0.007	<0.02	<0.01	<2	0.213	0.013	0.13	7.72	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646539	Drill Core	11.72	<2	11	17	0.05	<0.001	0.002	<0.02	<0.01	<2	0.217	0.013	0.13	7.79	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646540	Drill Core	11.42	<2	25	24	0.04	<0.001	0.002	<0.02	<0.01	<2	0.216	0.013	0.12	7.50	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646541	Drill Core	10.40	<2	21	24	0.08	<0.001	0.004	<0.02	<0.01	<2	0.225	0.013	0.12	7.26	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646542	Drill Core	12.11	<2	16	22	0.08	<0.001	0.009	<0.02	<0.01	<2	0.242	0.013	0.12	7.36	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 26, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000689.2

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
646514	Drill Core	2.22	<0.01	0.212	23.59	0.05	0.39	0.04	0.03	<0.01	0.27	0.015	0.116	0.007	1.26	4.08	N.A.
646515	Drill Core	1.74	<0.01	0.182	24.40	0.03	0.13	0.02	<0.01	<0.01	0.34	0.008	0.127	0.007	1.51	4.58	N.A.
646516	Drill Core	2.11	<0.01	0.122	25.24	0.02	0.12	0.02	<0.01	<0.01	0.15	0.003	0.102	0.005	1.47	4.71	N.A.
646517	Drill Core	2.00	<0.01	0.130	24.35	0.02	0.12	0.02	<0.01	<0.01	0.24	0.006	0.119	0.006	1.63	5.00	N.A.
646518	Drill Core	2.64	<0.01	0.262	23.92	0.03	0.14	0.02	<0.01	<0.01	0.21	0.004	0.105	0.006	1.56	4.95	N.A.
646519	Drill Core	3.90	<0.01	0.178	21.57	0.04	0.20	0.03	<0.01	<0.01	0.50	0.012	0.120	0.009	1.45	3.90	N.A.
646520A	Drill Core	0.69	<0.01	0.226	25.21	0.01	0.09	<0.01	<0.01	<0.01	0.31	0.006	0.117	0.007	1.18	4.01	N.A.
646520B	Drill Core	0.68	<0.01	0.244	25.05	0.01	0.09	<0.01	<0.01	<0.01	0.30	0.006	0.119	0.008	1.35	4.70	N.A.
646521	Drill Core	1.04	<0.01	0.187	26.21	0.01	0.09	0.01	<0.01	<0.01	0.20	0.005	0.102	0.006	1.74	5.45	N.A.
646522	Drill Core	2.57	<0.01	0.159	23.50	0.02	0.13	0.03	<0.01	<0.01	0.35	0.008	0.113	0.007	1.53	4.40	3.16
646523	Drill Core	2.86	0.02	0.138	18.20	0.07	1.98	0.93	0.18	<0.01	0.52	0.012	0.139	0.008	1.01	2.61	N.A.
646524	Drill Core	9.36	0.04	0.228	11.46	0.18	2.79	0.44	0.84	<0.01	0.46	0.015	0.066	0.006	0.58	1.02	N.A.
646525	Rock Pulp	3.17	<0.01	0.484	14.41	0.14	3.06	0.23	0.05	<0.01	0.90	0.099	0.263	0.013	1.31	1.61	N.A.
646526	Rock Pulp	1.14	<0.01	0.174	21.46	0.02	0.28	0.03	0.09	<0.01	3.04	0.051	0.404	0.028	2.22	3.27	N.A.
646527	Drill Core	7.41	<0.01	0.228	17.30	0.06	0.32	0.07	<0.01	<0.01	1.24	0.036	0.107	0.011	1.56	2.80	N.A.
646528	Drill Core	3.90	<0.01	0.241	21.25	0.04	0.20	0.04	<0.01	<0.01	0.73	0.022	0.086	0.010	1.38	3.61	N.A.
646529	Drill Core	6.47	<0.01	0.286	18.63	0.06	0.32	0.06	0.01	<0.01	0.69	0.020	0.069	0.009	1.45	3.40	N.A.
646530	Drill Core	2.01	0.02	0.002	0.31	0.07	7.17	3.44	1.16	<0.01	<0.01	<0.001	0.001	<0.001	0.13	0.11	N.A.
646531	Drill Core	8.19	<0.01	0.189	16.64	0.06	0.32	0.07	<0.01	<0.01	1.05	0.044	0.113	0.013	1.46	2.83	N.A.
646532	Drill Core	5.45	<0.01	0.125	19.59	0.04	0.23	0.05	<0.01	<0.01	0.40	0.016	0.106	0.008	1.13	3.58	3.26
646533	Drill Core	2.02	<0.01	0.147	23.71	0.02	0.14	0.03	<0.01	<0.01	0.24	0.015	0.102	0.006	1.29	4.96	N.A.
646534	Drill Core	2.23	<0.01	0.157	24.23	0.02	0.14	0.02	<0.01	<0.01	0.10	0.007	0.072	0.005	1.30	4.47	N.A.
646535	Drill Core	2.17	<0.01	0.125	23.99	0.02	0.14	0.02	<0.01	<0.01	0.08	0.003	0.078	0.005	1.51	5.02	N.A.
646536	Drill Core	1.70	<0.01	0.222	23.48	0.02	0.14	0.02	<0.01	<0.01	0.12	0.004	0.097	0.005	0.60	2.46	N.A.
646537	Drill Core	1.26	<0.01	0.191	24.79	0.02	0.11	0.01	<0.01	<0.01	0.08	0.002	0.075	0.004	0.64	2.45	N.A.
646538	Drill Core	1.14	<0.01	0.246	24.33	0.02	0.17	0.02	<0.01	<0.01	0.17	0.007	0.130	0.007	0.49	2.72	N.A.
646539	Drill Core	1.19	<0.01	0.207	25.15	0.01	0.10	0.01	<0.01	<0.01	0.07	0.002	0.070	0.004	0.70	2.82	N.A.
646540	Drill Core	1.46	<0.01	0.184	24.56	0.02	0.14	0.02	<0.01	<0.01	0.07	0.002	0.075	0.004	0.62	2.40	N.A.
646541	Drill Core	1.44	<0.01	0.191	24.48	0.03	0.16	0.01	<0.01	<0.01	0.11	0.005	0.103	0.005	0.66	2.81	N.A.
646542	Drill Core	1.53	<0.01	0.166	24.64	0.02	0.13	0.02	<0.01	<0.01	0.11	0.009	0.089	0.004	0.71	2.40	N.A.



ACME ANALYTICAL LABORATORIES LTD.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client:

Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.

Vancouver BC V6E 3V7 Canada

Project:

Turnagain

Report Date:

September 26, 2008

Page:

3 of 3

Part 1

CERTIFICATE OF ANALYSIS

SMI08000689.2

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646543	Drill Core	10.05	<2	5	12	0.22	<0.001	0.019	<0.02	<0.01	<2	0.222	0.015	0.12	7.66	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646544	Drill Core	11.45	<2	17	21	0.27	<0.001	0.026	<0.02	<0.01	<2	0.251	0.014	0.12	7.71	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646545	Drill Core	11.18	<2	29	39	0.36	<0.001	0.027	<0.02	<0.01	<2	0.309	0.016	0.12	8.28	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646546	Drill Core	10.94	<2	10	15	0.20	<0.001	0.017	<0.02	<0.01	<2	0.256	0.015	0.13	8.07	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646547	Drill Core	11.59	<2	4	8	0.15	<0.001	0.008	<0.02	<0.01	<2	0.181	0.014	0.14	7.75	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646548	Drill Core	9.25	<2	20	25	0.16	<0.001	0.011	<0.02	<0.01	<2	0.133	0.010	0.10	6.98	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646549	Drill Core	10.31	<2	14	20	0.19	<0.001	0.011	<0.02	<0.01	<2	0.120	0.011	0.11	7.64	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646550	Rock Pulp	0.03	I.S.	I.S.	I.S.	1.40	<0.001	0.031	<0.02	<0.01	<2	0.258	0.018	0.12	9.09	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646551	Rock Pulp	0.03	I.S.	I.S.	I.S.	0.46	<0.001	0.055	<0.02	0.02	<2	0.231	0.012	0.11	9.22	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646552	Drill Core	11.29	<2	3	5	0.29	<0.001	0.023	<0.02	<0.01	<2	0.206	0.013	0.13	7.86	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646553	Drill Core	11.30	<2	<3	6	0.26	<0.001	0.013	<0.02	<0.01	<2	0.217	0.014	0.14	8.14	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646554	Drill Core	10.91	<2	20	27	0.41	<0.001	0.056	<0.02	<0.01	<2	0.271	0.015	0.13	7.97	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646555	Drill Core	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.
646556	Drill Core	11.36	<2	22	31	0.70	<0.001	0.043	<0.02	<0.01	<2	0.314	0.017	0.13	8.29	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646557	Drill Core	10.80	<2	<3	7	1.13	<0.001	0.031	<0.02	<0.01	<2	0.118	0.018	0.14	10.37	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646558	Drill Core	10.79	<2	<3	7	0.85	<0.001	0.030	<0.02	<0.01	<2	0.132	0.016	0.15	10.24	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646559	Drill Core	11.58	<2	3	4	0.77	<0.001	0.023	<0.02	0.01	<2	0.120	0.017	0.14	10.86	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646560	Drill Core	2.02	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.002	<0.001	0.07	1.22	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
646561	Drill Core	11.01	<2	5	7	0.52	<0.001	0.016	<0.02	0.01	<2	0.146	0.014	0.12	8.51	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646562	Drill Core	11.25	<2	11	19	0.45	<0.001	0.010	<0.02	<0.01	<2	0.234	0.016	0.13	7.84	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 26, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000689.2

Method		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
Unit		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
MDL		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
646543	Drill Core	1.18	<0.01	0.146	25.14	0.01	0.10	0.01	<0.01	<0.01	0.28	0.017	0.109	0.005	0.84	2.56	N.A.
646544	Drill Core	1.17	<0.01	0.165	24.75	0.03	0.24	0.01	0.05	<0.01	0.28	0.026	0.154	0.006	0.81	2.36	N.A.
646545	Drill Core	0.49	<0.01	0.213	25.27	0.02	0.13	<0.01	<0.01	<0.01	0.34	0.028	0.219	0.008	0.90	2.84	N.A.
646546	Drill Core	0.50	<0.01	0.172	26.49	0.01	0.11	<0.01	<0.01	<0.01	0.21	0.017	0.131	0.006	0.80	2.56	N.A.
646547	Drill Core	1.89	<0.01	0.233	24.25	0.03	0.21	0.02	0.03	<0.01	0.17	0.008	0.091	0.005	0.61	2.18	N.A.
646548	Drill Core	3.48	<0.01	0.180	20.36	0.03	0.24	0.03	<0.01	<0.01	0.17	0.010	0.100	0.006	0.36	1.82	N.A.
646549	Drill Core	5.29	<0.01	0.193	18.57	0.05	0.32	0.04	0.03	<0.01	0.21	0.010	0.093	0.007	0.39	1.83	N.A.
646550	Rock Pulp	0.73	<0.01	0.136	24.21	0.02	0.32	<0.01	0.07	<0.01	1.23	0.032	0.247	0.013	0.95	2.68	N.A.
646551	Rock Pulp	4.30	<0.01	0.979	13.14	0.19	4.04	0.30	0.11	<0.01	0.49	0.055	0.198	0.007	0.41	0.36	N.A.
646552	Drill Core	2.53	<0.01	0.146	23.61	0.03	0.16	0.02	0.01	<0.01	0.31	0.023	0.115	0.005	0.72	2.10	3.18
646553	Drill Core	2.18	<0.01	0.133	24.19	0.02	0.16	0.02	0.02	<0.01	0.29	0.013	0.124	0.006	0.71	2.13	N.A.
646554	Drill Core	2.81	<0.01	0.228	22.95	0.03	0.19	0.03	<0.01	<0.01	0.46	0.056	0.193	0.008	0.74	1.97	N.A.
646555	Drill Core	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.
646556	Drill Core	2.16	<0.01	0.185	22.57	0.02	0.17	0.02	<0.01	<0.01	0.71	0.041	0.244	0.010	0.86	1.91	N.A.
646557	Drill Core	3.92	<0.01	0.291	19.78	0.04	0.25	0.04	0.01	<0.01	1.14	0.029	0.108	0.012	0.70	1.65	N.A.
646558	Drill Core	2.66	<0.01	0.281	21.33	0.03	0.21	0.03	<0.01	<0.01	0.90	0.030	0.122	0.011	0.69	1.98	N.A.
646559	Drill Core	2.21	<0.01	0.303	20.75	0.05	0.36	0.02	0.04	<0.01	0.77	0.022	0.104	0.012	0.60	1.61	N.A.
646560	Drill Core	1.90	0.01	0.004	0.32	0.07	7.12	3.32	1.14	<0.01	0.01	<0.001	0.001	<0.001	0.16	0.12	N.A.
646561	Drill Core	2.58	<0.01	0.177	20.45	0.11	0.70	0.03	0.11	<0.01	0.52	0.016	0.118	0.009	0.53	1.53	N.A.
646562	Drill Core	1.61	<0.01	0.127	24.40	0.07	0.43	0.02	0.09	<0.01	0.47	0.010	0.143	0.007	0.65	1.83	N.A.

QUALITY CONTROL REPORT

SMI08000689.2

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
Pulp Duplicates																					
646520A	Drill Core	10.10	3	30	23	0.27	<0.001	0.005	<0.02	<0.01	<2	0.197	0.012	0.13	8.27	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646520A	QC																				
646520B	Drill Core		<2	22	21	0.25	<0.001	0.006	<0.02	<0.01	<2	0.192	0.012	0.13	8.51	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646520B	QC					0.27															
646527	Drill Core	12.04	<2	13	10	1.26	<0.001	0.033	<0.02	<0.01	<2	0.130	0.015	0.13	8.11	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646527	QC					1.25															
646532	Drill Core	11.35	<2	38	47	0.36	<0.001	0.015	<0.02	<0.01	<2	0.155	0.012	0.12	7.25	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646532	QC					<0.001	0.015	<0.02	<0.01	<2	0.153	0.012	0.12	7.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
646551	Rock Pulp	0.03	I.S.	I.S.	I.S.	0.46	<0.001	0.055	<0.02	0.02	<2	0.231	0.012	0.11	9.22	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
REP 646551	QC																				
646562	Drill Core	11.25	<2	11	19	0.45	<0.001	0.010	<0.02	<0.01	<2	0.234	0.016	0.13	7.84	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646562	QC																				
Core Reject Duplicates																					
646524	Drill Core	11.36	<2	17	8	0.46	<0.001	0.014	<0.02	<0.01	<2	0.067	0.008	0.12	5.97	<0.02	0.03	<0.001	<0.01	<0.01	0.01
DUP 646524	QC		<2	17	9	0.49	<0.001	0.014	<0.02	<0.01	<2	0.067	0.008	0.12	6.05	<0.02	0.03	<0.001	<0.01	<0.01	0.01
646559	Drill Core	11.58	<2	3	4	0.77	<0.001	0.023	<0.02	0.01	<2	0.120	0.017	0.14	10.86	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
DUP 646559	QC		<2	<3	3	0.74	<0.001	0.024	<0.02	0.02	<2	0.118	0.017	0.14	10.22	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
Reference Materials																					
STD CDN-PGMS-14	Standard		237	105	408																
STD CDN-PGMS-14	Standard		231	137	420																
STD CDN-PGMS-14	Standard		239	101	420																
STD CSC	Standard					4.22															
STD CSC	Standard					4.18															
STD CSC	Standard					4.26															
STD FA10R	Standard		450	435	444																
STD FA10R	Standard		467	458	459																
STD FA10R	Standard		489	475	488																
STD OREAS76A	Standard					18.08															

QUALITY CONTROL REPORT

SMI08000689.2

Method		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
Unit		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
Pulp Duplicates																	
646520A	Drill Core	0.69	<0.01	0.226	25.21	0.01	0.09	<0.01	<0.01	<0.01	0.31	0.006	0.117	0.007	1.18	4.01	N.A.
REP 646520A	QC											0.006	0.119	0.007	1.21	4.11	
646520B	Drill Core	0.68	<0.01	0.244	25.05	0.01	0.09	<0.01	<0.01	<0.01	0.30	0.006	0.119	0.008	1.35	4.70	N.A.
REP 646520B	QC																
646527	Drill Core	7.41	<0.01	0.228	17.30	0.06	0.32	0.07	<0.01	<0.01	1.24	0.036	0.107	0.011	1.56	2.80	N.A.
REP 646527	QC																
646532	Drill Core	5.45	<0.01	0.125	19.59	0.04	0.23	0.05	<0.01	<0.01	0.40	0.016	0.106	0.008	1.13	3.58	3.26
REP 646532	QC	5.33	<0.01	0.125	19.34	0.04	0.23	0.05	<0.01	<0.01	0.40						
646551	Rock Pulp	4.30	<0.01	0.979	13.14	0.19	4.04	0.30	0.11	<0.01	0.49	0.055	0.198	0.007	0.41	0.36	N.A.
REP 646551	QC											0.053	0.193	0.007	0.39	0.33	
646562	Drill Core	1.61	<0.01	0.127	24.40	0.07	0.43	0.02	0.09	<0.01	0.47	0.010	0.143	0.007	0.65	1.83	N.A.
REP 646562	QC											0.009	0.141	0.007	0.63	1.75	
Core Reject Duplicates																	
646524	Drill Core	9.36	0.04	0.228	11.46	0.18	2.79	0.44	0.84	<0.01	0.46	0.015	0.066	0.006	0.58	1.02	N.A.
DUP 646524	QC	9.55	0.04	0.229	11.60	0.18	2.76	0.43	0.84	<0.01	0.49	0.015	0.064	0.006	0.57	0.97	N.A.
646559	Drill Core	2.21	<0.01	0.303	20.75	0.05	0.36	0.02	0.04	<0.01	0.77	0.022	0.104	0.012	0.60	1.61	N.A.
DUP 646559	QC	2.18	<0.01	0.308	21.29	0.06	0.38	0.02	0.05	<0.01	0.79	0.021	0.098	0.011	0.60	1.74	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard																
STD CSC	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																

QUALITY CONTROL REPORT

SMI08000689.2

		WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
STD OREAS76A	Standard					17.31															
STD OREAS76A	Standard					18.04															
STD R3NI	Standard																				
STD R3NI	Standard																				
STD R3NI	Standard																				
STD R3T	Standard					0.078	0.816	2.00	4.10	199	0.546	0.062	0.09	33.11	0.03	<0.01	0.024	0.04	<0.01	0.02	
STD R3T	Standard					0.076	0.819	1.97	4.13	192	0.535	0.062	0.09	32.81	0.03	<0.01	0.023	0.04	<0.01	0.02	
STD R3T	Standard					0.078	0.810	2.03	4.07	211	0.546	0.068	0.09	32.62	0.03	<0.01	0.024	0.04	<0.01	0.02	
STD R3T	Standard					0.079	0.826	2.05	4.12	218	0.553	0.069	0.09	32.94	0.03	<0.01	0.024	0.04	<0.01	0.02	
STD SF-3A_NI	Standard																				
STD R3T Expected						0.077	0.805	1.98	4.1	190	0.525	0.061	0.09	34.17	0.04	0.01	0.024	0.04			
STD FA10R Expected			485	472	476																
STD CDN-PGMS-14			259	119	451																
STD R3NI Expected																					
STD SF-3A_NI Expected																					
STD CSC Expected						4.19															
STD OREAS76A Expected						18															
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank					<0.02															
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank																				
BLK	Blank																				

QUALITY CONTROL REPORT

SMI08000689.2

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
STD OREAS76A	Standard																
STD OREAS76A	Standard																
STD R3NI	Standard											0.522	0.454	0.063	11.48	0.20	
STD R3NI	Standard											0.522	0.454	0.063	11.48	0.20	
STD R3NI	Standard											0.714	0.393	0.051	4.46	0.15	
STD R3T	Standard	2.20	0.05	0.020	1.68	0.17	2.44	0.32	0.59	<0.01	16.65						
STD R3T	Standard	2.20	0.05	0.020	1.67	0.17	2.42	0.31	0.59	<0.01	16.42						
STD R3T	Standard	2.26	0.06	0.020	1.69	0.18	2.42	0.32	0.59	<0.01	17.38						
STD R3T	Standard	2.29	0.05	0.023	1.70	0.18	2.45	0.32	0.60	<0.01	17.01						
STD SF-3A_NI	Standard											0.056	0.333	0.018	3.64	3.51	
STD R3T Expected		2.23	0.05	0.02	1.64		2.44	0.31	0.59								
STD FA10R Expected																	
STD CDN-PGMS-14																	
STD R3NI Expected												0.42					
STD SF-3A_NI Expected												0.3205					
STD CSC Expected																	
STD OREAS76A Expected																	
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	

QUALITY CONTROL REPORT

SMI08000689.2

		WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
BLK	Blank					<0.02															
BLK	Blank					<0.02															
Prep Wash																					
G1	Prep Blank	<0.01	<2	4	<2	N.A.	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.34	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank	<0.01	6	<3	<2	N.A.	0.001	<0.001	<0.02	<0.01	<2	0.001	<0.001	0.07	2.31	<0.02	0.07	<0.001	<0.01	<0.01	<0.01

QUALITY CONTROL REPORT

SMI08000689.2

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NIS	8NIS	8NIS	8NIS	8NIS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
BLK	Blank																
BLK	Blank																
Prep Wash																	
G1	Prep Blank	2.34	0.07	<0.001	0.64	0.23	8.29	2.55	3.06	<0.01	0.02	<0.001	<0.001	<0.001	0.21	0.06	N.A.
G1	Prep Blank	2.40	0.07	0.003	0.62	0.22	8.41	2.70	3.03	<0.01	<0.01	<0.001	<0.001	<0.001	0.19	0.05	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By:

Receiving Lab:

Received:

Report Date:

Page:

Canada-Smithers

August 11, 2008

September 12, 2008

1 of 3

CERTIFICATE OF ANALYSIS

SMI08000717.1

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-255B
 P.O. Number
 Number of Samples: 53

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	49	Crush split and pulverize drill core to 200 mesh		
3B	53	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	53	Analysis by Leco	0.1	Completed
7TD	53	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	53	Leached with H2O2 + NH4 citrate	1	Completed
Specific Gravity	2	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 12, 2008

Page: 2 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000717.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646563	Drill Core	11.25	<2	11	9	0.36	<0.001	0.010	<0.02	<0.01	<2	0.227	0.013	0.13	7.55	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646564	Drill Core	11.03	7	6	7	0.26	<0.001	0.006	<0.02	<0.01	<2	0.211	0.012	0.13	7.52	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646565	Drill Core	10.52	47	26	6	0.47	<0.001	0.010	<0.02	<0.01	<2	0.227	0.013	0.12	7.69	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646566	Drill Core	11.41	<2	<3	8	0.26	<0.001	0.007	<0.02	<0.01	<2	0.240	0.012	0.13	7.63	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646567	Drill Core	11.83	<2	<3	<2	0.40	<0.001	0.012	<0.02	<0.01	<2	0.156	0.013	0.14	8.12	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646568	Drill Core	9.84	2	<3	4	0.40	<0.001	0.007	<0.02	<0.01	<2	0.125	0.015	0.12	7.96	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646569	Drill Core	11.01	4	<3	6	0.39	<0.001	0.009	<0.02	<0.01	<2	0.181	0.012	0.13	7.30	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646570	Drill Core	10.80	<2	<3	2	0.27	<0.001	0.005	<0.02	<0.01	<2	0.198	0.011	0.12	7.54	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646571	Drill Core	10.34	12	<3	<2	0.23	<0.001	0.007	<0.02	<0.01	<2	0.202	0.010	0.12	7.21	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646572	Drill Core	10.34	5	8	9	1.05	<0.001	0.055	<0.02	0.01	<2	0.180	0.017	0.13	9.45	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646573	Drill Core	10.97	4	5	12	0.67	<0.001	0.043	<0.02	<0.01	<2	0.262	0.017	0.12	8.51	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646574	Drill Core	11.38	13	45	50	1.94	<0.001	0.137	<0.02	<0.01	<2	0.628	0.028	0.13	9.48	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646575	Rock Pulp	0.04	I.S.	I.S.	I.S.	1.00	<0.001	0.096	<0.02	<0.01	2	0.345	0.016	0.05	8.94	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646576	Rock Pulp	0.04	I.S.	I.S.	I.S.	4.24	<0.001	0.048	<0.02	<0.01	<2	0.409	0.028	0.12	12.72	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646577	Drill Core	10.85	19	102	111	0.96	<0.001	0.103	<0.02	<0.01	2	0.653	0.018	0.12	7.75	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646578	Drill Core	11.52	6	32	37	0.80	<0.001	0.094	<0.02	<0.01	3	0.517	0.017	0.12	8.07	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646579	Drill Core	10.48	9	24	33	1.52	<0.001	0.143	<0.02	<0.01	<2	0.642	0.023	0.11	8.42	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646580A	Drill Core	11.30	13	76	77	1.31	<0.001	0.109	<0.02	<0.01	2	0.674	0.020	0.12	8.09	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646580B	Drill Core		17	74	79	1.34	<0.001	0.113	<0.02	<0.01	3	0.699	0.021	0.12	8.32	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646581	Drill Core	10.17	19	54	66	1.66	<0.001	0.185	<0.02	<0.01	4	0.721	0.023	0.12	8.82	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646582	Drill Core	10.79	30	94	80	2.99	<0.001	0.232	<0.02	<0.01	3	0.807	0.034	0.12	10.92	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646583	Drill Core	11.76	10	39	41	1.70	<0.001	0.098	<0.02	<0.01	<2	0.450	0.021	0.12	9.77	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646584	Drill Core	11.03	5	33	49	1.48	<0.001	0.065	<0.02	<0.01	<2	0.431	0.020	0.12	9.31	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646585	Drill Core	10.88	3	28	37	0.73	<0.001	0.034	<0.02	<0.01	2	0.308	0.016	0.12	8.03	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646586	Drill Core	10.75	4	34	44	0.81	<0.001	0.039	<0.02	<0.01	<2	0.373	0.017	0.10	7.50	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646587	Drill Core	10.40	<2	25	11	0.59	<0.001	0.014	<0.02	<0.01	<2	0.202	0.011	0.10	7.78	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646588	Drill Core	11.14	4	10	19	1.49	<0.001	0.054	<0.02	0.02	<2	0.139	0.014	0.14	9.69	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
646589	Drill Core	10.32	7	23	32	2.43	<0.001	0.073	<0.02	0.01	<2	0.418	0.026	0.14	11.74	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646590	Drill Core	2.69	<2	8	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.001	<0.001	0.07	1.13	<0.02	0.08	<0.001	<0.01	<0.01	<0.01
646591	Drill Core	11.19	5	4	14	0.91	<0.001	0.040	<0.02	<0.01	<2	0.228	0.015	0.14	9.20	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 12, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000717.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S		Cu	Ni	Co	Fe	Mg	SG
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
646563	Drill Core	1.52	<0.01	0.133	23.87	0.07	0.39	0.02	0.04	<0.01	0.32	0.011	0.147	0.008	1.14	3.47	N.A.
646564	Drill Core	1.56	<0.01	0.119	23.87	0.06	0.37	0.02	0.06	<0.01	0.24	0.006	0.130	0.007	1.09	3.48	N.A.
646565	Drill Core	2.07	<0.01	0.130	22.78	0.07	0.40	0.02	0.07	<0.01	0.41	0.011	0.177	0.009	1.23	3.44	N.A.
646566	Drill Core	2.14	<0.01	0.120	24.35	0.07	0.32	0.02	0.05	<0.01	0.20	0.008	0.145	0.006	1.05	3.19	N.A.
646567	Drill Core	2.84	<0.01	0.143	22.95	0.08	0.38	0.03	0.05	<0.01	0.31	0.012	0.098	0.007	1.08	3.00	N.A.
646568	Drill Core	1.60	<0.01	0.153	22.10	0.09	0.52	0.02	0.04	<0.01	0.34	0.007	0.104	0.013	0.83	3.33	N.A.
646569	Drill Core	2.96	<0.01	0.100	22.77	0.12	0.50	0.03	0.04	<0.01	0.34	0.009	0.119	0.007	1.09	3.13	N.A.
646570	Drill Core	2.93	<0.01	0.086	22.36	0.11	0.47	0.03	0.06	<0.01	0.22	0.006	0.131	0.007	1.03	3.05	N.A.
646571	Drill Core	2.27	<0.01	0.130	23.29	0.06	0.30	0.02	0.08	<0.01	0.19	0.008	0.145	0.007	0.89	3.01	N.A.
646572	Drill Core	1.41	<0.01	0.240	23.27	0.04	0.25	<0.01	0.04	<0.01	0.78	0.057	0.161	0.015	0.95	2.26	N.A.
646573	Drill Core	1.12	<0.01	0.269	23.10	0.04	0.30	<0.01	0.07	<0.01	0.54	0.045	0.232	0.014	0.93	2.42	N.A.
646574	Drill Core	0.86	<0.01	0.259	23.58	0.03	0.23	<0.01	0.04	<0.01	1.36	0.140	0.580	0.026	1.56	2.14	N.A.
646575	Rock Pulp	3.23	<0.01	0.374	14.82	0.14	2.78	0.23	0.05	<0.01	0.83	0.095	0.264	0.013	1.21	1.52	N.A.
646576	Rock Pulp	1.15	0.01	0.186	21.27	0.02	0.29	0.03	0.09	<0.01	2.92	0.050	0.398	0.029	1.97	2.96	N.A.
646577	Drill Core	0.43	<0.01	0.204	24.32	0.04	0.24	<0.01	0.05	<0.01	0.83	0.109	0.595	0.015	1.32	2.45	N.A.
646578	Drill Core	0.32	<0.01	0.219	25.00	0.04	0.25	<0.01	0.06	<0.01	0.68	0.098	0.438	0.013	1.16	2.39	N.A.
646579	Drill Core	0.18	<0.01	0.168	23.57	0.03	0.25	<0.01	0.05	<0.01	1.23	0.143	0.582	0.022	1.62	2.79	N.A.
646580A	Drill Core	0.99	<0.01	0.270	23.81	0.05	0.39	<0.01	0.08	<0.01	1.06	0.115	0.627	0.019	1.39	2.33	N.A.
646580B	Drill Core	0.95	<0.01	0.270	23.52	0.06	0.40	<0.01	0.09	<0.01	1.09	0.121	0.667	0.019	1.48	2.32	N.A.
646581	Drill Core	1.03	<0.01	0.258	23.17	0.05	0.35	<0.01	0.08	<0.01	1.27	0.195	0.670	0.021	1.58	2.16	N.A.
646582	Drill Core	1.09	<0.01	0.188	23.25	0.04	0.26	0.01	0.04	<0.01	2.13	0.191	0.729	0.029	2.10	2.28	N.A.
646583	Drill Core	0.56	<0.01	0.182	24.15	0.05	0.36	<0.01	0.10	<0.01	1.34	0.095	0.388	0.017	1.46	2.62	N.A.
646584	Drill Core	2.16	0.02	0.167	21.07	0.04	0.35	0.02	<0.01	<0.01	1.16	0.068	0.400	0.016	1.32	2.02	N.A.
646585	Drill Core	0.78	0.02	0.131	24.54	0.04	0.26	<0.01	0.01	<0.01	0.60	0.033	0.230	0.011	1.08	2.85	N.A.
646586	Drill Core	0.89	<0.01	0.123	23.41	0.05	0.52	<0.01	0.13	<0.01	0.67	0.038	0.299	0.013	1.05	2.71	N.A.
646587	Drill Core	2.26	0.01	0.138	20.18	0.13	1.05	<0.01	0.28	<0.01	0.47	0.015	0.183	0.010	0.55	1.26	N.A.
646588	Drill Core	4.23	<0.01	0.197	18.20	0.08	0.77	0.02	0.04	<0.01	1.15	0.055	0.124	0.012	1.12	1.63	N.A.
646589	Drill Core	1.47	<0.01	0.218	20.32	0.08	0.47	0.01	0.02	<0.01	1.71	0.071	0.389	0.025	1.55	2.00	N.A.
646590	Drill Core	2.00	0.02	0.003	0.32	0.07	7.56	3.41	1.15	<0.01	<0.01	<0.001	0.002	<0.001	0.11	0.08	N.A.
646591	Drill Core	2.58	<0.01	0.186	20.78	0.05	0.32	0.02	<0.01	<0.01	0.71	0.042	0.204	0.013	1.07	2.35	N.A.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

ACME ANALYTICAL LABORATORIES LTD.

www.acmelab.com

Client:

Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
Vancouver BC V6E 3V7 Canada

Project:

Turnagain

Report Date:

September 12, 2008

Page:

3 of 3

Part 1

CERTIFICATE OF ANALYSIS

SMI08000717.1

Method	WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646592	Drill Core	10.35	15	42	56	2.61	<0.001	0.117	<0.02	<0.01	<2	0.744	0.026	0.15	11.04	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646593	Drill Core	10.15	7	3	6	0.40	<0.001	0.015	<0.02	<0.01	<2	0.147	0.011	0.15	8.68	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646594	Drill Core	10.23	6	6	14	1.30	<0.001	0.029	<0.02	0.01	<2	0.162	0.013	0.15	9.75	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
646595	Drill Core	10.75	2	<3	3	1.35	<0.001	0.041	<0.02	<0.01	<2	0.053	0.008	0.13	8.81	<0.02	<0.01	<0.001	<0.01	<0.01	0.04
646596	Drill Core	10.60	5	12	13	0.81	<0.001	0.022	<0.02	<0.01	<2	0.188	0.014	0.17	9.72	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646597	Drill Core	10.78	8	9	21	0.66	<0.001	0.016	<0.02	0.01	<2	0.198	0.015	0.17	9.55	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646598	Drill Core	10.84	<2	48	16	1.68	<0.001	0.022	<0.02	<0.01	<2	0.176	0.015	0.14	11.82	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646599	Drill Core	11.66	<2	<3	8	2.74	0.002	0.035	<0.02	<0.01	<2	0.080	0.012	0.14	10.73	<0.02	<0.01	<0.001	<0.01	<0.01	0.04
646600	Rock Pulp	0.04	I.S.	I.S.	I.S.	0.49	<0.001	0.055	<0.02	0.01	<2	0.224	0.011	0.11	8.59	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646601	Rock Pulp	0.03	I.S.	I.S.	I.S.	1.42	<0.001	0.031	<0.02	<0.01	<2	0.252	0.017	0.12	8.85	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646602	Drill Core	11.84	46	22	19	2.71	0.002	0.036	<0.02	<0.01	<2	0.150	0.016	0.13	11.83	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
646603	Drill Core	11.72	3	10	9	2.05	0.001	0.031	<0.02	<0.01	<2	0.175	0.016	0.13	9.77	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646604	Drill Core	10.40	3	19	22	1.65	<0.001	0.030	<0.02	<0.01	<2	0.147	0.013	0.12	7.82	<0.02	0.03	<0.001	<0.01	<0.01	<0.01
646605	Drill Core	11.27	<2	14	21	0.73	<0.001	0.029	<0.02	<0.01	<2	0.227	0.016	0.12	7.16	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646606	Drill Core	10.34	<2	58	61	0.19	<0.001	0.025	<0.02	<0.01	<2	0.258	0.014	0.12	7.32	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646607	Drill Core	11.01	<2	17	20	0.11	<0.001	0.003	<0.02	<0.01	<2	0.209	0.014	0.13	7.49	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646608	Drill Core	10.45	<2	<3	3	0.07	<0.001	0.002	<0.02	<0.01	<2	0.125	0.009	0.14	6.46	<0.02	0.02	<0.001	<0.01	<0.01	<0.01
646609	Drill Core	10.57	<2	15	22	0.15	<0.001	0.004	<0.02	<0.01	<2	0.223	0.014	0.12	7.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646610A	Drill Core	9.71	3	15	20	1.17	<0.001	0.051	<0.02	<0.01	<2	0.279	0.017	0.15	9.36	<0.02	0.02	<0.001	<0.01	<0.01	<0.01
646610B	Drill Core		4	18	20	1.16	<0.001	0.051	<0.02	<0.01	<2	0.261	0.016	0.15	8.98	<0.02	0.02	<0.001	<0.01	<0.01	<0.01
646611	Drill Core	10.26	<2	16	8	0.26	<0.001	0.012	<0.02	<0.01	<2	0.143	0.008	0.13	6.08	<0.02	0.02	<0.001	<0.01	<0.01	0.01
646612	Drill Core	10.34	<2	54	55	0.29	<0.001	0.013	<0.02	<0.01	<2	0.271	0.013	0.10	6.49	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646613	Drill Core	10.16	<2	51	60	0.62	<0.001	0.021	<0.02	<0.01	<2	0.134	0.009	0.12	6.53	<0.02	0.04	<0.001	<0.01	<0.01	0.02



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 12, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000717.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
646592	Drill Core	2.50	<0.01	0.143	20.77	0.04	0.29	0.03	<0.01	<0.01	1.92	0.108	0.716	0.025	2.09	2.04	3.11
646593	Drill Core	3.46	<0.01	0.167	20.08	0.05	0.30	0.02	<0.01	<0.01	0.33	0.016	0.128	0.009	0.67	1.86	N.A.
646594	Drill Core	3.28	<0.01	0.190	19.94	0.05	0.35	0.02	<0.01	<0.01	1.02	0.030	0.143	0.012	0.96	1.57	N.A.
646595	Drill Core	9.23	0.02	0.142	14.37	0.07	0.43	0.06	<0.01	<0.01	0.98	0.042	0.049	0.007	1.04	0.83	N.A.
646596	Drill Core	3.54	<0.01	0.189	21.22	0.06	0.40	0.03	<0.01	<0.01	0.66	0.021	0.157	0.010	0.88	1.96	N.A.
646597	Drill Core	2.18	<0.01	0.185	21.98	0.04	0.26	0.02	<0.01	<0.01	0.51	0.016	0.162	0.010	1.00	2.76	N.A.
646598	Drill Core	4.45	<0.01	0.145	18.88	0.05	0.25	0.03	<0.01	<0.01	1.22	0.022	0.146	0.013	1.16	1.86	N.A.
646599	Drill Core	8.89	<0.01	0.143	14.23	0.07	0.36	0.07	<0.01	<0.01	2.06	0.037	0.077	0.012	1.59	1.08	N.A.
646600	Rock Pulp	4.23	<0.01	0.747	14.06	0.18	3.83	0.33	0.11	<0.01	0.46	0.055	0.182	0.007	0.55	0.62	N.A.
646601	Rock Pulp	0.71	<0.01	0.145	24.79	0.02	0.31	<0.01	0.07	<0.01	1.06	0.030	0.218	0.014	1.26	3.97	N.A.
646602	Drill Core	6.35	<0.01	0.120	17.16	0.05	0.27	0.05	<0.01	<0.01	1.83	0.037	0.136	0.014	1.53	1.72	N.A.
646603	Drill Core	4.46	<0.01	0.206	20.86	0.03	0.20	0.04	<0.01	<0.01	1.43	0.032	0.142	0.013	1.53	2.15	N.A.
646604	Drill Core	2.43	0.03	0.177	17.77	0.10	2.83	1.12	0.36	<0.01	1.18	0.030	0.129	0.011	0.97	1.48	N.A.
646605	Drill Core	1.18	<0.01	0.204	23.77	0.01	0.62	<0.01	0.21	<0.01	0.54	0.028	0.166	0.011	0.89	2.87	N.A.
646606	Drill Core	0.44	<0.01	0.201	27.24	<0.01	0.06	<0.01	<0.01	<0.01	0.16	0.022	0.162	0.008	0.61	3.58	N.A.
646607	Drill Core	0.50	<0.01	0.200	26.63	0.03	0.30	<0.01	0.05	<0.01	0.09	0.003	0.109	0.007	0.61	3.46	N.A.
646608	Drill Core	2.63	0.03	0.128	18.24	0.11	3.25	0.55	1.47	<0.01	0.06	0.002	0.066	0.004	0.33	1.54	N.A.
646609	Drill Core	0.16	<0.01	0.106	26.82	<0.01	0.22	<0.01	0.07	<0.01	0.13	0.004	0.146	0.009	0.58	3.31	N.A.
646610A	Drill Core	2.48	<0.01	0.137	19.53	0.05	1.01	0.17	0.07	<0.01	0.84	0.050	0.257	0.016	0.74	1.56	N.A.
646610B	Drill Core	2.63	0.01	0.132	19.87	0.05	1.11	0.18	0.07	<0.01	0.79	0.049	0.246	0.015	0.69	1.35	N.A.
646611	Drill Core	3.26	0.05	0.060	16.18	0.18	3.24	1.00	1.02	<0.01	0.23	0.012	0.110	0.006	0.44	1.96	N.A.
646612	Drill Core	0.16	<0.01	0.113	27.04	<0.01	0.04	<0.01	<0.01	<0.01	0.23	0.013	0.180	0.009	0.78	4.19	3.10
646613	Drill Core	3.27	0.07	0.082	13.66	0.25	4.29	1.28	1.21	<0.01	0.52	0.021	0.123	0.008	0.60	1.16	N.A.

QUALITY CONTROL REPORT

SMI08000717.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
Pulp Duplicates																					
REP 646572	QC																				
REP 646572	QC					1.03															
646576	Rock Pulp	0.04	I.S.	I.S.	I.S.	4.24	<0.001	0.048	<0.02	<0.01	<2	0.409	0.028	0.12	12.72	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646576	QC						<0.001	0.048	<0.02	<0.01	<2	0.417	0.028	0.12	12.43	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646597	Drill Core	10.78	8	9	21	0.66	<0.001	0.016	<0.02	0.01	<2	0.198	0.015	0.17	9.55	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
REP 646597	QC																				
646607	Drill Core	11.01	<2	17	20	0.11	<0.001	0.003	<0.02	<0.01	<2	0.209	0.014	0.13	7.49	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646607	QC					0.11															
Core Reject Duplicates																					
646572	Drill Core	10.34	5	8	9	1.05	<0.001	0.055	<0.02	0.01	<2	0.180	0.017	0.13	9.45	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
DUP 646572	QC		4	4	11	1.02	<0.001	0.056	<0.02	<0.01	<2	0.176	0.017	0.13	9.23	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646606	Drill Core	10.34	<2	58	61	0.19	<0.001	0.025	<0.02	<0.01	<2	0.258	0.014	0.12	7.32	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
DUP 646606	QC		2	48	56	0.18	<0.001	0.025	<0.02	<0.01	<2	0.262	0.014	0.12	7.39	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
Reference Materials																					
STD CDN-PGMS-14	Standard		246	125	410																
STD CDN-PGMS-14	Standard		230	112	413																
STD CDN-PGMS-14	Standard		239	112	425																
STD CDN-PGMS-14	Standard		234	115	419																
STD CSC	Standard					4.28															
STD CSC	Standard					4.27															
STD FA10R	Standard		474	470	475																
STD FA10R	Standard		486	475	486																
STD FA10R	Standard		447	441	446																
STD FA10R	Standard		464	472	456																
STD OREAS76A	Standard					17.35															
STD OREAS76A	Standard					17.50															
STD R3NI	Standard																				
STD SF-3A_NI	Standard																				

QUALITY CONTROL REPORT

SMI08000717.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG	
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%		
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
Pulp Duplicates																	
REP 646572	QC										0.056	0.161	0.015	0.94	2.24		
REP 646572	QC																
646576	Rock Pulp	1.15	0.01	0.186	21.27	0.02	0.29	0.03	0.09	<0.01	2.92	0.050	0.398	0.029	1.97	2.96	N.A.
REP 646576	QC	1.15	0.02	0.188	21.03	0.02	0.29	0.03	0.09	<0.01	2.75						
646597	Drill Core	2.18	<0.01	0.185	21.98	0.04	0.26	0.02	<0.01	<0.01	0.51	0.016	0.162	0.010	1.00	2.76	N.A.
REP 646597	QC										0.017	0.167	0.011	1.03	2.83		
646607	Drill Core	0.50	<0.01	0.200	26.63	0.03	0.30	<0.01	0.05	<0.01	0.09	0.003	0.109	0.007	0.61	3.46	N.A.
REP 646607	QC																
Core Reject Duplicates																	
646572	Drill Core	1.41	<0.01	0.240	23.27	0.04	0.25	<0.01	0.04	<0.01	0.78	0.057	0.161	0.015	0.95	2.26	N.A.
DUP 646572	QC	1.40	<0.01	0.236	22.83	0.04	0.24	<0.01	0.04	<0.01	0.77	0.059	0.159	0.015	0.95	2.29	3.09
646606	Drill Core	0.44	<0.01	0.201	27.24	<0.01	0.06	<0.01	<0.01	<0.01	0.16	0.022	0.162	0.008	0.61	3.58	N.A.
DUP 646606	QC	0.41	<0.01	0.222	27.41	<0.01	0.07	<0.01	<0.01	<0.01	0.15	0.023	0.159	0.008	0.65	3.78	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																
STD OREAS76A	Standard																
STD R3NI	Standard										0.507	0.446	0.055	6.18	0.62		
STD SF-3A_NI	Standard										0.056	0.333	0.018	3.64	3.51		

QUALITY CONTROL REPORT

SMI08000717.1

		WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
STD SF-3T	Standard						0.030	0.775	0.90	1.08	51	0.347	0.017	0.42	8.14	<0.02	0.04	0.004	<0.01	<0.01	0.01
STD SF-3T	Standard						0.031	0.794	0.92	1.10	52	0.353	0.018	0.43	8.28	<0.02	0.04	0.005	<0.01	<0.01	0.01
STD SF-3T	Standard						0.032	0.771	0.93	1.08	51	0.347	0.017	0.42	7.99	<0.02	0.04	0.005	<0.01	<0.01	0.01
STD SF-3T	Standard						0.031	0.777	0.93	1.09	52	0.348	0.018	0.42	7.99	<0.02	0.04	0.004	<0.01	<0.01	0.01
STD SF-3T	Standard						0.032	0.768	0.95	1.08	54	0.350	0.018	0.43	8.08	<0.02	0.04	0.005	<0.01	<0.01	0.01
STD SF-3T	Standard						0.033	0.779	0.96	1.10	54	0.351	0.018	0.44	8.18	<0.02	0.04	0.005	<0.01	<0.01	0.01
STD SF-3T Expected							0.032	0.7723	0.961	1.0672	52	0.35	0.0181	0.432	8.33	0.004	0.044	0.00475	0.00111	0.00048	0.0143
STD CSC Expected							4.19														
STD OREAS76A Expected							18														
STD R3NI Expected																					
STD SF-3A_NI Expected																					
STD FA10R Expected			485	472	476																
STD CDN-PGMS-14			259	119	451																
BLK	Blank						<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
BLK	Blank						<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
BLK	Blank						<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
BLK	Blank						<0.02														
BLK	Blank						<0.02														
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
Prep Wash																					

QUALITY CONTROL REPORT

SMI08000717.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
STD SF-3T	Standard	4.01	0.05	0.016	4.57	0.19	5.33	2.05	2.46	<0.01	3.95						
STD SF-3T	Standard	4.07	0.05	0.017	4.67	0.20	5.42	2.07	2.50	<0.01	4.14						
STD SF-3T	Standard	4.04	0.06	0.016	4.59	0.19	5.42	2.06	2.47	<0.01	3.84						
STD SF-3T	Standard	4.04	0.06	0.017	4.60	0.20	5.41	2.08	2.47	<0.01	3.89						
STD SF-3T	Standard	4.05	0.06	0.020	4.59	0.19	5.43	2.11	2.49	<0.01	3.97						
STD SF-3T	Standard	4.07	0.06	0.020	4.62	0.20	5.45	2.10	2.51	<0.01	4.05						
STD SF-3T Expected		4.1	0.06	0.02074	4.67	0.19	5.43	2.06	2.47	0.00043	3.5						
STD CSC Expected																	
STD OREAS76A Expected																	
STD R3NI Expected													0.42				
STD SF-3A_NI Expected													0.3205				
STD FA10R Expected																	
STD CDN-PGMS-14																	
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank																
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank																
BLK	Blank																
Prep Wash																	

QUALITY CONTROL REPORT

SMI08000717.1

		WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
G1	Prep Blank	<0.01	2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.08	2.34	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank	<0.01	2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.21	<0.02	0.07	<0.001	<0.01	<0.01	<0.01

QUALITY CONTROL REPORT

SMI08000717.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
G1	Prep Blank	2.32	0.08	0.001	0.68	0.24	7.74	2.78	3.10	<0.01	<0.01	<0.001	<0.001	<0.001	0.21	0.03	N.A.
G1	Prep Blank	2.22	0.07	<0.001	0.62	0.21	7.42	2.57	2.92	<0.01	0.04	<0.001	<0.001	<0.001	0.20	0.03	N.A.

Hole 08-256



ACME ANALYTICAL LABORATORIES LTD.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client:

Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.

Vancouver BC V6E 3V7 Canada

Submitted By:

Receiving Lab:

Received:

Report Date:

Page:

Canada-Smithers

August 11, 2008

September 08, 2008

1 of 3

CERTIFICATE OF ANALYSIS

SMI08000718.1

CLIENT JOB INFORMATION

Project: Turnagain
Shipment ID: C08-256A
P.O. Number
Number of Samples: 48

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
1060 - 1090 W. Georgia St.
Vancouver BC V6E 3V7
Canada

CC:

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	44	Crush split and pulverize drill core to 200 mesh		
3B	48	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	48	Analysis by Leco	0.1	Completed
7TD	48	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	48	Leached with H2O2 + NH4 citrate	1	Completed
Specific Gravity	3	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 08, 2008

Page: 2 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000718.1

Method	WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646614	Drill Core	7.43	<2	14	27	0.19	<0.001	0.006	<0.02	<0.01	<2	0.159	0.012	0.16	8.97	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646615	Drill Core	11.20	<2	<3	3	0.19	<0.001	0.008	<0.02	0.01	<2	0.159	0.012	0.17	9.51	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646616	Drill Core	11.51	<2	<3	<2	0.21	<0.001	0.013	<0.02	<0.01	<2	0.205	0.012	0.14	8.36	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646617	Drill Core	12.93	<2	11	15	0.16	<0.001	0.005	<0.02	<0.01	<2	0.187	0.012	0.15	8.62	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646618	Drill Core	11.96	<2	8	7	0.18	<0.001	0.006	<0.02	<0.01	<2	0.185	0.012	0.15	8.39	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646619	Drill Core	11.65	<2	26	13	0.26	<0.001	0.008	<0.02	<0.01	<2	0.138	0.010	0.14	7.11	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646620	Drill Core	2.04	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.001	<0.001	0.07	1.03	<0.02	0.08	<0.001	<0.01	<0.01	<0.01
646621	Drill Core	11.28	<2	14	7	0.82	<0.001	0.029	<0.02	<0.01	<2	0.118	0.011	0.12	6.83	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646622	Drill Core	10.48	<2	<3	3	0.47	<0.001	0.021	<0.02	<0.01	<2	0.075	0.009	0.09	4.82	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646623	Drill Core	10.66	3	15	15	0.50	<0.001	0.063	<0.02	<0.01	<2	0.178	0.012	0.11	6.10	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646624	Drill Core	10.96	3	18	13	0.30	<0.001	0.078	<0.02	<0.01	<2	0.261	0.014	0.12	7.08	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646625	Rock Pulp	0.04	I.S.	I.S.	I.S.	4.14	0.001	0.047	<0.02	<0.01	<2	0.403	0.027	0.13	13.45	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646626	Rock Pulp	0.04	I.S.	I.S.	I.S.	1.06	<0.001	0.093	<0.02	<0.01	<2	0.328	0.015	0.05	9.04	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646627	Drill Core	10.98	4	61	65	0.26	<0.001	0.046	<0.02	<0.01	<2	0.252	0.013	0.12	7.00	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646628	Drill Core	11.11	<2	39	43	0.23	<0.001	0.047	<0.02	<0.01	<2	0.217	0.013	0.12	6.49	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646629	Drill Core	12.18	<2	8	11	0.19	<0.001	0.049	<0.02	<0.01	<2	0.214	0.013	0.13	6.92	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646630	Drill Core	11.39	<2	30	29	0.72	<0.001	0.126	<0.02	<0.01	<2	0.393	0.018	0.13	8.04	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646631	Drill Core	12.04	<2	25	25	0.26	<0.001	0.052	<0.02	<0.01	<2	0.220	0.015	0.13	7.33	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646632	Drill Core	10.37	3	46	49	0.20	<0.001	0.035	<0.02	<0.01	<2	0.231	0.014	0.13	7.11	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646633	Drill Core	10.73	<2	35	41	0.09	<0.001	0.006	<0.02	<0.01	<2	0.232	0.013	0.12	6.48	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646634	Drill Core	10.74	<2	16	10	0.16	<0.001	0.013	<0.02	<0.01	<2	0.219	0.012	0.11	6.38	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646635	Drill Core	11.08	<2	25	33	0.15	<0.001	0.008	<0.02	<0.01	<2	0.262	0.013	0.11	6.46	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646636	Drill Core	9.92	<2	24	32	0.10	<0.001	0.003	<0.02	<0.01	<2	0.260	0.012	0.12	6.60	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646637	Drill Core	10.75	<2	17	19	0.06	<0.001	0.001	<0.02	<0.01	<2	0.242	0.012	0.12	6.39	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646638	Drill Core	10.16	<2	8	5	0.04	<0.001	0.001	<0.02	<0.01	<2	0.231	0.012	0.11	6.42	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646639	Drill Core	9.72	3	79	92	0.22	<0.001	0.014	<0.02	<0.01	<2	0.315	0.013	0.10	6.33	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646640A	Drill Core	10.73	2	21	30	0.12	<0.001	0.006	<0.02	<0.01	<2	0.249	0.012	0.10	6.39	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646640B	Drill Core		<2	21	27	0.12	<0.001	0.006	<0.02	<0.01	2	0.249	0.012	0.10	6.42	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646641	Drill Core	9.83	<2	20	21	0.16	<0.001	0.005	<0.02	<0.01	<2	0.240	0.013	0.11	6.33	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646642	Drill Core	10.91	2	15	8	0.10	<0.001	0.002	<0.02	<0.01	<2	0.232	0.012	0.11	6.40	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 08, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000718.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S		Cu	Ni	Co	Fe	Mg	SG
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
646614	Drill Core	3.08	<0.01	0.173	23.77	0.04	0.18	0.03	<0.01	<0.01	0.21	0.006	0.079	0.005	1.22	3.36	N.A.
646615	Drill Core	2.86	<0.01	0.307	23.50	0.04	0.29	0.04	0.02	<0.01	0.20	0.008	0.092	0.006	1.27	3.67	N.A.
646616	Drill Core	2.25	<0.01	0.176	24.84	0.03	0.22	0.02	<0.01	<0.01	0.07	0.013	0.113	0.006	0.96	3.20	N.A.
646617	Drill Core	2.83	<0.01	0.149	23.66	0.04	0.41	0.03	<0.01	<0.01	0.18	0.005	0.099	0.006	0.95	3.01	N.A.
646618	Drill Core	2.89	<0.01	0.176	24.17	0.03	0.20	0.03	<0.01	<0.01	0.20	0.006	0.103	0.006	0.99	3.27	N.A.
646619	Drill Core	6.10	<0.01	0.174	20.41	0.04	0.27	0.06	<0.01	<0.01	0.30	0.008	0.090	0.005	0.81	2.39	N.A.
646620	Drill Core	1.87	0.01	0.002	0.25	0.07	6.74	3.61	1.16	<0.01	0.01	<0.001	<0.001	<0.001	0.08	0.07	N.A.
646621	Drill Core	8.56	<0.01	0.134	17.55	0.07	0.45	0.06	<0.01	<0.01	0.78	0.029	0.103	0.009	1.03	2.13	N.A.
646622	Drill Core	10.04	<0.01	0.127	15.58	0.06	0.40	0.09	<0.01	<0.01	0.51	0.022	0.069	0.007	0.74	1.95	N.A.
646623	Drill Core	7.00	<0.01	0.188	20.06	0.05	0.28	0.06	0.02	<0.01	0.53	0.061	0.117	0.007	1.07	2.84	N.A.
646624	Drill Core	2.25	<0.01	0.207	24.67	0.02	0.14	0.02	<0.01	<0.01	0.31	0.072	0.149	0.006	1.14	3.91	N.A.
646625	Rock Pulp	1.18	<0.01	0.177	21.62	0.02	0.29	0.03	0.10	<0.01	2.95	0.031	0.396	0.026	2.25	3.19	N.A.
646626	Rock Pulp	3.21	<0.01	0.391	14.93	0.15	2.79	0.22	0.05	<0.01	0.88	0.095	0.268	0.012	1.30	1.72	N.A.
646627	Drill Core	1.82	<0.01	0.249	24.84	0.02	0.17	0.02	<0.01	<0.01	0.13	0.047	0.153	0.007	1.00	3.66	N.A.
646628	Drill Core	1.88	<0.01	0.351	24.65	0.03	0.21	0.02	<0.01	<0.01	0.23	0.048	0.114	0.006	0.97	3.55	N.A.
646629	Drill Core	1.91	<0.01	0.274	25.41	0.02	0.15	0.02	<0.01	<0.01	0.20	0.050	0.102	0.005	0.96	3.43	N.A.
646630	Drill Core	1.61	<0.01	0.230	25.49	0.02	0.13	0.02	<0.01	<0.01	0.70	0.122	0.287	0.010	1.35	3.16	N.A.
646631	Drill Core	1.65	<0.01	0.141	25.65	0.02	0.13	0.02	0.01	<0.01	0.25	0.053	0.124	0.006	1.02	3.51	N.A.
646632	Drill Core	1.19	<0.01	0.196	26.60	0.02	0.15	0.01	0.01	<0.01	0.19	0.034	0.121	0.006	0.90	3.57	3.22
646633	Drill Core	0.82	<0.01	0.216	27.08	0.02	0.14	<0.01	0.01	<0.01	0.09	0.006	0.091	0.005	0.94	3.84	N.A.
646634	Drill Core	0.48	<0.01	0.143	26.30	0.02	0.14	<0.01	<0.01	<0.01	0.16	0.013	0.118	0.007	0.89	4.74	N.A.
646635	Drill Core	0.78	<0.01	0.185	26.26	0.02	0.18	<0.01	0.02	<0.01	0.14	0.008	0.124	0.006	1.01	4.50	N.A.
646636	Drill Core	0.76	<0.01	0.172	26.63	0.02	0.14	<0.01	0.01	<0.01	0.10	0.003	0.106	0.005	1.07	4.66	N.A.
646637	Drill Core	0.82	<0.01	0.164	26.63	0.02	0.12	<0.01	0.02	<0.01	0.06	0.001	0.083	0.004	1.07	4.41	N.A.
646638	Drill Core	1.06	<0.01	0.179	26.75	0.02	0.14	<0.01	0.02	<0.01	0.03	<0.001	0.056	0.003	0.94	3.67	N.A.
646639	Drill Core	0.97	<0.01	0.129	25.80	0.03	0.24	<0.01	0.02	<0.01	0.21	0.015	0.199	0.007	0.96	4.70	N.A.
646640A	Drill Core	1.03	<0.01	0.117	25.85	0.02	0.19	<0.01	0.02	<0.01	0.11	0.006	0.112	0.006	0.88	4.01	N.A.
646640B	Drill Core	1.06	<0.01	0.109	25.83	0.02	0.19	<0.01	0.02	<0.01	0.11	0.006	0.109	0.005	0.89	4.03	N.A.
646641	Drill Core	1.00	<0.01	0.167	26.25	0.02	0.17	<0.01	0.01	<0.01	0.13	0.005	0.120	0.006	0.75	4.07	N.A.
646642	Drill Core	1.23	<0.01	0.221	25.82	0.02	0.17	0.01	0.02	<0.01	0.09	0.002	0.095	0.005	0.92	4.19	3.19



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 08, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000718.1

Method	WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646643	Drill Core	10.66	<2	12	4	0.08	<0.001	0.002	<0.02	<0.01	<2	0.223	0.012	0.10	6.65	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646644	Drill Core	10.75	<2	9	7	0.06	<0.001	0.003	<0.02	<0.01	3	0.206	0.012	0.12	6.98	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646645	Drill Core	11.25	<2	9	7	0.07	<0.001	0.005	<0.02	<0.01	<2	0.217	0.013	0.12	7.10	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646646	Drill Core	10.69	<2	<3	8	0.11	<0.001	0.003	<0.02	<0.01	<2	0.204	0.012	0.12	6.55	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646647	Drill Core	9.62	<2	8	6	0.23	<0.001	0.011	<0.02	<0.01	<2	0.184	0.012	0.12	6.91	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646648	Drill Core	11.09	<2	10	20	0.29	<0.001	0.007	<0.02	<0.01	<2	0.112	0.011	0.13	7.69	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646649	Drill Core	10.35	<2	14	26	0.46	<0.001	0.014	<0.02	<0.01	<2	0.208	0.011	0.12	6.93	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646650	Rock Pulp	0.04	I.S.	I.S.	I.S.	0.48	<0.001	0.051	<0.02	0.02	<2	0.223	0.012	0.11	8.94	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646651	Rock Pulp	0.04	I.S.	I.S.	I.S.	1.43	<0.001	0.029	<0.02	<0.01	<2	0.242	0.016	0.11	8.56	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646652	Drill Core	11.06	<2	21	30	0.26	<0.001	0.010	<0.02	<0.01	<2	0.212	0.012	0.13	7.40	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646653	Drill Core	10.44	<2	34	43	0.31	<0.001	0.016	<0.02	<0.01	<2	0.245	0.012	0.12	6.85	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646654	Drill Core	10.30	<2	64	91	0.59	<0.001	0.025	<0.02	<0.01	<2	0.359	0.014	0.12	7.15	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646655	Drill Core	10.58	3	72	60	2.29	<0.001	0.055	<0.02	<0.01	<2	0.156	0.013	0.14	8.76	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646656	Drill Core	11.17	<2	30	20	2.31	<0.001	0.055	<0.02	<0.01	<2	0.065	0.010	0.15	8.77	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
646657	Drill Core	12.39	<2	29	10	2.63	<0.001	0.050	<0.02	<0.01	<2	0.035	0.009	0.14	9.08	<0.02	<0.01	<0.001	<0.01	<0.01	0.04
646658	Drill Core	11.95	5	22	15	4.60	0.002	0.118	<0.02	<0.01	<2	0.046	0.013	0.16	11.66	<0.02	<0.01	<0.001	<0.01	<0.01	0.06
646659	Drill Core	12.42	3	58	38	2.69	<0.001	0.101	<0.02	<0.01	<2	0.109	0.013	0.13	8.92	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
646660	Drill Core	10.28	11	74	73	1.63	<0.001	0.123	<0.02	<0.01	<2	0.327	0.019	0.14	9.41	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 08, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000718.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
646643	Drill Core	1.11	<0.01	0.265	26.14	0.02	0.17	<0.01	0.02	<0.01	0.06	0.001	0.094	0.005	0.99	4.19	N.A.
646644	Drill Core	1.83	<0.01	0.259	25.36	0.03	0.20	0.02	0.03	<0.01	0.04	0.002	0.069	0.004	0.95	3.54	N.A.
646645	Drill Core	1.73	<0.01	0.243	25.77	0.03	0.26	0.02	0.06	<0.01	0.07	0.004	0.081	0.004	1.08	4.05	N.A.
646646	Drill Core	1.65	<0.01	0.162	26.65	0.03	0.22	0.02	0.04	<0.01	0.09	0.003	0.083	0.005	0.99	4.00	N.A.
646647	Drill Core	1.21	<0.01	0.126	25.04	0.03	0.18	0.01	0.01	<0.01	0.20	0.012	0.132	0.009	0.86	4.16	N.A.
646648	Drill Core	4.54	<0.01	0.130	20.96	0.12	0.76	0.04	0.16	<0.01	0.25	0.007	0.072	0.007	1.10	3.53	N.A.
646649	Drill Core	2.27	<0.01	0.103	23.62	0.12	0.66	0.02	0.14	<0.01	0.39	0.009	0.154	0.008	1.30	3.91	N.A.
646650	Rock Pulp	4.32	<0.01	1.224	14.05	0.19	4.15	0.33	0.11	<0.01	0.42	0.057	0.189	0.008	0.63	0.76	N.A.
646651	Rock Pulp	0.68	<0.01	0.117	25.54	0.02	0.28	<0.01	0.07	<0.01	1.12	0.004	0.224	0.014	1.42	3.99	N.A.
646652	Drill Core	2.41	<0.01	0.156	25.37	0.07	0.45	0.03	0.10	<0.01	0.22	0.009	0.127	0.006	1.26	4.10	3.22
646653	Drill Core	2.32	<0.01	0.165	24.04	0.04	0.29	0.02	0.07	<0.01	0.26	0.002	0.163	0.007	1.32	3.97	N.A.
646654	Drill Core	1.77	<0.01	0.152	24.42	0.07	0.45	0.02	0.14	<0.01	0.52	0.014	0.282	0.010	1.28	3.29	N.A.
646655	Drill Core	6.80	<0.01	0.095	16.22	0.13	0.81	0.06	0.11	<0.01	1.71	0.063	0.152	0.012	1.75	1.62	N.A.
646656	Drill Core	10.33	<0.01	0.097	13.05	0.20	1.07	0.08	0.07	<0.01	1.77	0.060	0.066	0.010	2.24	0.96	N.A.
646657	Drill Core	12.32	<0.01	0.070	10.94	0.17	0.98	0.08	0.01	<0.01	1.95	0.054	0.036	0.009	2.52	0.68	N.A.
646658	Drill Core	10.90	0.01	0.073	10.13	0.22	0.95	0.10	0.24	<0.01	3.55	0.123	0.049	0.014	4.23	0.58	N.A.
646659	Drill Core	10.90	<0.01	0.122	12.50	0.13	0.66	0.08	<0.01	<0.01	2.14	0.104	0.112	0.013	2.52	0.84	N.A.
646660	Drill Core	1.62	<0.01	0.152	20.36	0.04	0.22	<0.01	<0.01	<0.01	1.31	0.094	0.300	0.019	1.16	1.40	N.A.

QUALITY CONTROL REPORT

SMI08000718.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
Pulp Duplicates																				
REP G1	QC																			
646620	Drill Core	2.04	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.001	<0.001	0.07	1.03	<0.02	0.08	<0.001	<0.01	<0.01
REP 646620	QC					<0.02														
646623	Drill Core	10.66	3	15	15	0.50	<0.001	0.063	<0.02	<0.01	<2	0.178	0.012	0.11	6.10	<0.02	<0.01	<0.001	<0.01	<0.01
REP 646623	QC		<2	16	14															
646630	Drill Core	11.39	<2	30	29	0.72	<0.001	0.126	<0.02	<0.01	<2	0.393	0.018	0.13	8.04	<0.02	<0.01	<0.001	<0.01	<0.01
REP 646630	QC																			
646636	Drill Core	9.92	<2	24	32	0.10	<0.001	0.003	<0.02	<0.01	<2	0.260	0.012	0.12	6.60	<0.02	<0.01	<0.001	<0.01	<0.01
REP 646636	QC					<0.001	0.003	<0.02	<0.01	<2	0.254	0.012	0.11	6.46	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646639	Drill Core	9.72	3	79	92	0.22	<0.001	0.014	<0.02	<0.01	<2	0.315	0.013	0.10	6.33	<0.02	<0.01	<0.001	<0.01	<0.01
REP 646639	QC					<0.001	0.015	<0.02	<0.01	2	0.312	0.013	0.10	6.25	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646643	Drill Core	10.66	<2	12	4	0.08	<0.001	0.002	<0.02	<0.01	<2	0.223	0.012	0.10	6.65	<0.02	<0.01	<0.001	<0.01	<0.01
REP 646643	QC																			
646654	Drill Core	10.30	<2	64	91	0.59	<0.001	0.025	<0.02	<0.01	<2	0.359	0.014	0.12	7.15	<0.02	<0.01	<0.001	<0.01	<0.01
REP 646654	QC																			
646658	Drill Core	11.95	5	22	15	4.60	0.002	0.118	<0.02	<0.01	<2	0.046	0.013	0.16	11.66	<0.02	<0.01	<0.001	<0.01	<0.01
REP 646658	QC						0.002	0.118	<0.02	<0.01	<2	0.045	0.013	0.16	11.61	<0.02	<0.01	<0.001	<0.01	<0.01
Core Reject Duplicates																				
646637	Drill Core	10.75	<2	17	19	0.06	<0.001	0.001	<0.02	<0.01	<2	0.242	0.012	0.12	6.39	<0.02	<0.01	<0.001	<0.01	<0.01
DUP 646637	QC		<2	23	23	0.06	<0.001	0.001	<0.02	<0.01	<2	0.250	0.013	0.11	6.38	<0.02	<0.01	<0.001	<0.01	<0.01
Reference Materials																				
STD CDN-PGMS-14	Standard		246	125	410															
STD CDN-PGMS-14	Standard		283	119	475															
STD CDN-PGMS-14	Standard		229	101	408															
STD CSC	Standard					4.28														
STD CSC	Standard					4.26														
STD CSC	Standard					4.25														
STD FA10R	Standard		474	470	475															

QUALITY CONTROL REPORT

SMI08000718.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG	
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%		
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
Pulp Duplicates																	
REP G1	QC										<0.001	<0.001	<0.001	0.21	0.09		
646620	Drill Core	1.87	0.01	0.002	0.25	0.07	6.74	3.61	1.16	<0.01	0.01	<0.001	<0.001	<0.001	0.08	0.07	N.A.
REP 646620	QC																
646623	Drill Core	7.00	<0.01	0.188	20.06	0.05	0.28	0.06	0.02	<0.01	0.53	0.061	0.117	0.007	1.07	2.84	N.A.
REP 646623	QC																
646630	Drill Core	1.61	<0.01	0.230	25.49	0.02	0.13	0.02	<0.01	<0.01	0.70	0.122	0.287	0.010	1.35	3.16	N.A.
REP 646630	QC										0.123	0.288	0.010	1.33	3.12		
646636	Drill Core	0.76	<0.01	0.172	26.63	0.02	0.14	<0.01	0.01	<0.01	0.10	0.003	0.106	0.005	1.07	4.66	N.A.
REP 646636	QC	0.75	<0.01	0.172	26.25	0.02	0.14	<0.01	0.01	<0.01	0.10						
646639	Drill Core	0.97	<0.01	0.129	25.80	0.03	0.24	<0.01	0.02	<0.01	0.21	0.015	0.199	0.007	0.96	4.70	N.A.
REP 646639	QC	0.97	<0.01	0.131	25.86	0.03	0.23	<0.01	0.02	<0.01	0.20						
646643	Drill Core	1.11	<0.01	0.265	26.14	0.02	0.17	<0.01	0.02	<0.01	0.06	0.001	0.094	0.005	0.99	4.19	N.A.
REP 646643	QC										0.001	0.095	0.005	1.00	4.25		
646654	Drill Core	1.77	<0.01	0.152	24.42	0.07	0.45	0.02	0.14	<0.01	0.52	0.014	0.282	0.010	1.28	3.29	N.A.
REP 646654	QC										0.010	0.280	0.010	1.33	3.28		
646658	Drill Core	10.90	0.01	0.073	10.13	0.22	0.95	0.10	0.24	<0.01	3.55	0.123	0.049	0.014	4.23	0.58	N.A.
REP 646658	QC	10.95	0.01	0.069	10.32	0.22	0.94	0.10	0.23	<0.01	3.49						
Core Reject Duplicates																	
646637	Drill Core	0.82	<0.01	0.164	26.63	0.02	0.12	<0.01	0.02	<0.01	0.06	0.001	0.083	0.004	1.07	4.41	N.A.
DUP 646637	QC	0.83	<0.01	0.191	27.15	0.01	0.13	<0.01	0.02	<0.01	0.08	0.001	0.087	0.004	1.06	4.38	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard																
STD CSC	Standard																
STD CSC	Standard																
STD FA10R	Standard																

QUALITY CONTROL REPORT

SMI08000718.1

	WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
STD FA10R	Standard	448	452	452																
STD FA10R	Standard	494	487	496																
STD FA10R	Standard	459	443	452																
STD OREAS76A	Standard				18.14															
STD OREAS76A	Standard				17.58															
STD OREAS76A	Standard				17.61															
STD R3T	Standard				0.076	0.826	2.00	4.13	199	0.539	0.062	0.09	33.06	0.02	<0.01	0.024	0.04	<0.01	0.02	
STD R3T	Standard				0.078	0.827	2.02	4.19	196	0.545	0.063	0.09	33.07	0.02	<0.01	0.024	0.04	<0.01	0.02	
STD R3T	Standard				0.077	0.828	2.06	4.27	208	0.550	0.063	0.10	33.42	0.03	<0.01	0.024	0.03	<0.01	0.02	
STD R3T	Standard				0.077	0.838	2.06	4.26	199	0.553	0.063	0.10	33.60	0.03	<0.01	0.024	0.03	<0.01	0.02	
STD SF-3A_NI	Standard																			
STD SF-3A_NI	Standard																			
STD SF-3A_NI	Standard																			
STD SF-3T	Standard				0.031	0.786	0.94	1.07	51	0.354	0.018	0.42	7.82	<0.02	0.04	0.004	<0.01	<0.01	0.01	
STD SF-3T	Standard				0.031	0.782	0.94	1.08	51	0.352	0.018	0.43	7.93	<0.02	0.04	0.004	<0.01	<0.01	0.01	
STD R3T Expected					0.077	0.805	1.98	4.1	190	0.525	0.061	0.09	34.17	0.04	0.01	0.024	0.04			
STD SF-3T Expected					0.032	0.7723	0.961	1.0672	52	0.35	0.0181	0.432	8.33	0.004	0.044	0.00475	0.00111	0.00048	0.0143	
STD CSC Expected					4.19															
STD OREAS76A Expected					18															
STD FA10R Expected		485	472	476																
STD CDN-PGMS-14		259	119	451																
STD SF-3A_NI Expected																				
BLK	Blank				<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	
BLK	Blank				<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	
BLK	Blank				<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	
BLK	Blank	<2	<3	<2																
BLK	Blank	<2	<3	<2																
BLK	Blank	<2	<3	<2																
BLK	Blank	<2	<3	<2																

QUALITY CONTROL REPORT

SMI08000718.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																
STD OREAS76A	Standard																
STD OREAS76A	Standard																
STD R3T	Standard	2.22	0.05	0.020	1.69	0.17	2.44	0.31	0.60	<0.01	16.47						
STD R3T	Standard	2.22	0.05	0.020	1.69	0.17	2.45	0.32	0.60	<0.01	16.47						
STD R3T	Standard	2.28	0.05	0.022	1.70	0.18	2.51	0.32	0.60	<0.01	16.87						
STD R3T	Standard	2.29	0.05	0.022	1.72	0.19	2.51	0.32	0.60	<0.01	16.82						
STD SF-3A_NI	Standard											0.046	0.318	0.016	3.58	3.20	
STD SF-3A_NI	Standard											0.056	0.333	0.018	3.64	3.51	
STD SF-3A_NI	Standard											0.091	0.343	0.018	4.03	3.42	
STD SF-3T	Standard	4.09	0.05	0.016	4.58	0.20	5.48	2.07	2.47	<0.01	3.93						
STD SF-3T	Standard	4.14	0.05	0.016	4.56	0.20	5.59	2.08	2.44	<0.01	3.90						
STD R3T Expected		2.23	0.05	0.02	1.64		2.44	0.31	0.59								
STD SF-3T Expected		4.1	0.06	0.02074	4.67	0.19	5.43	2.06	2.47	0.00043	3.5						
STD CSC Expected																	
STD OREAS76A Expected																	
STD FA10R Expected																	
STD CDN-PGMS-14																	
STD SF-3A_NI Expected																	0.3205
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																

QUALITY CONTROL REPORT

SMI08000718.1

		WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
BLK	Blank					<0.02															
BLK	Blank					<0.02															
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank					<0.02															
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.001	<0.001	0.08	2.39	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank	<0.01	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.001	<0.001	0.08	2.40	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank																				

QUALITY CONTROL REPORT

SMI08000718.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NIS	8NIS	8NIS	8NIS	8NIS	G8SG	
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
Prep Wash																	
G1	Prep Blank	2.35	0.08	<0.001	0.66	0.24	7.77	2.61	1.99	<0.01	0.01						N.A.
G1	Prep Blank	2.33	0.08	<0.001	0.70	0.25	7.48	2.65	2.25	<0.01	0.02	<0.001	<0.001	<0.001	0.14	0.05	N.A.
G1	Prep Blank											<0.001	<0.001	<0.001	0.19	0.09	



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By:

Receiving Lab:

Received:

Report Date:

Page:

Canada-Smithers

August 07, 2008

September 05, 2008

1 of 3

CERTIFICATE OF ANALYSIS

SMI08000699.1

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-256B
 P.O. Number
 Number of Samples: 45

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	41	Crush split and pulverize drill core to 200 mesh		
3B	45	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	45	Analysis by Leco	0.1	Completed
7TD	45	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	45	Leached with H2O2 + NH4 citrate	1	Completed
Specific Gravity	3	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

ACME ANALYTICAL LABORATORIES LTD.

www.acmelab.com

Client:

Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
Vancouver BC V6E 3V7 Canada

Project:

Turnagain

Report Date:

September 05, 2008

Page:

2 of 3

Part 1

CERTIFICATE OF ANALYSIS

SMI08000699.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646661	Drill Core	10.38	<2	4	6	0.13	<0.001	0.002	<0.02	<0.01	<2	0.215	0.013	0.14	7.86	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646662	Drill Core	10.07	<2	5	5	0.14	<0.001	0.002	<0.02	<0.01	<2	0.199	0.013	0.15	8.06	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646663	Drill Core	10.51	<2	12	18	0.45	<0.001	0.018	<0.02	<0.01	<2	0.110	0.010	0.13	7.55	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646664	Drill Core	10.87	3	8	9	0.45	<0.001	0.013	<0.02	<0.01	<2	0.191	0.012	0.13	7.65	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646665	Drill Core	11.33	3	19	29	1.94	<0.001	0.084	<0.02	0.01	<2	0.293	0.021	0.13	10.50	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646666	Drill Core	11.12	7	26	39	5.99	<0.001	0.204	<0.02	<0.01	<2	0.655	0.043	0.13	15.04	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646667	Drill Core	11.56	9	28	82	11.20	<0.001	0.323	<0.02	<0.01	<2	1.117	0.071	0.13	22.62	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646668	Drill Core	10.57	6	21	19	1.96	<0.001	0.067	<0.02	<0.01	<2	0.294	0.018	0.11	8.70	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646669	Drill Core	10.24	3	21	22	0.87	<0.001	0.055	<0.02	0.01	<2	0.367	0.017	0.11	7.97	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646670A	Drill Core	10.22	4	15	18	0.62	<0.001	0.037	<0.02	<0.01	<2	0.330	0.015	0.11	7.39	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646670B	Drill Core		4	15	20	0.64	<0.001	0.039	<0.02	<0.01	<2	0.347	0.015	0.11	7.55	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646671	Drill Core	10.18	3	3	9	0.55	<0.001	0.044	<0.02	<0.01	<2	0.206	0.015	0.13	8.15	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646672	Drill Core	10.67	<2	<3	5	0.33	<0.001	0.014	<0.02	<0.01	<2	0.166	0.013	0.13	7.49	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646673	Drill Core	9.87	<2	8	10	0.76	<0.001	0.030	<0.02	<0.01	<2	0.204	0.016	0.12	8.22	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646674	Drill Core	10.95	<2	32	46	3.88	<0.001	0.206	<0.02	<0.01	<2	0.511	0.035	0.13	13.48	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646675	Rock Pulp	0.02	I.S.	I.S.	I.S.	4.28	<0.001	0.049	<0.02	<0.01	<2	0.398	0.028	0.12	13.41	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646676	Rock Pulp	0.02	I.S.	I.S.	I.S.	0.50	<0.001	0.055	<0.02	0.02	<2	0.225	0.011	0.11	9.24	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646677	Drill Core	11.66	<2	17	29	1.32	<0.001	0.047	<0.02	<0.01	<2	0.338	0.021	0.13	9.50	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646678	Drill Core	11.00	<2	31	43	0.21	<0.001	0.005	<0.02	<0.01	<2	0.343	0.015	0.11	6.74	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646679	Drill Core	10.51	<2	13	16	0.12	<0.001	0.004	<0.02	<0.01	<2	0.241	0.013	0.12	7.10	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646680	Drill Core	2.73	<2	3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.002	<0.001	0.07	0.99	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
646681	Drill Core	11.10	<2	19	17	0.12	<0.001	0.011	<0.02	<0.01	<2	0.235	0.013	0.12	7.11	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646682	Drill Core	11.45	<2	8	11	0.14	<0.001	0.006	<0.02	<0.01	<2	0.223	0.013	0.13	7.25	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646683	Drill Core	10.23	<2	14	14	0.16	<0.001	0.011	<0.02	<0.01	<2	0.216	0.013	0.11	7.64	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646684	Drill Core	10.31	<2	20	18	0.22	<0.001	0.028	<0.02	<0.01	<2	0.222	0.013	0.11	7.43	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646685	Drill Core	10.69	<2	26	29	0.35	<0.001	0.016	<0.02	<0.01	<2	0.264	0.014	0.12	7.77	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646686	Drill Core	10.63	<2	37	44	0.55	<0.001	0.022	<0.02	<0.01	<2	0.289	0.015	0.14	8.83	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646687	Drill Core	10.56	<2	<3	<2	0.74	<0.001	0.034	<0.02	<0.01	<2	0.280	0.015	0.13	8.57	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646688	Drill Core	9.80	9	47	46	0.79	<0.001	0.072	<0.02	<0.01	<2	0.242	0.017	0.11	8.41	<0.02	0.02	<0.001	<0.01	<0.01	<0.01
646689	Drill Core	8.74	2	33	50	1.58	<0.001	0.126	<0.02	<0.01	<2	0.217	0.021	0.12	9.34	<0.02	0.03	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 05, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000699.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
646661	Drill Core	0.34	<0.01	0.210	24.59	0.03	0.32	<0.01	0.07	<0.01	0.20	0.003	0.125	0.007	0.39	1.70	N.A.
646662	Drill Core	0.29	<0.01	0.216	24.64	0.03	0.23	<0.01	0.02	<0.01	0.14	0.002	0.107	0.006	0.31	1.08	3.02
646663	Drill Core	6.71	<0.01	0.103	17.29	0.14	0.58	0.05	0.03	<0.01	0.45	0.018	0.091	0.007	0.40	1.02	N.A.
646664	Drill Core	3.93	<0.01	0.125	20.93	0.09	0.37	0.03	0.03	<0.01	0.43	0.012	0.146	0.008	0.38	0.91	N.A.
646665	Drill Core	1.07	<0.01	0.188	21.48	0.06	0.36	<0.01	0.08	<0.01	1.60	0.082	0.293	0.020	0.88	1.41	N.A.
646666	Drill Core	0.23	0.01	0.165	21.42	0.03	0.18	<0.01	0.03	<0.01	3.99	0.193	0.670	0.043	1.68	1.06	N.A.
646667	Drill Core	0.10	<0.01	0.161	18.12	0.02	0.15	<0.01	<0.01	<0.01	7.95	0.319	1.156	0.074	4.37	1.54	N.A.
646668	Drill Core	2.39	<0.01	0.113	19.46	0.06	0.56	<0.01	0.04	<0.01	1.60	0.063	0.297	0.018	0.73	0.75	N.A.
646669	Drill Core	0.58	<0.01	0.169	22.77	0.05	0.42	<0.01	0.09	<0.01	0.81	0.052	0.347	0.015	0.69	1.27	N.A.
646670A	Drill Core	0.62	<0.01	0.200	23.54	0.04	0.37	<0.01	0.07	<0.01	0.55	0.039	0.315	0.012	0.63	1.26	N.A.
646670B	Drill Core	0.62	<0.01	0.200	23.49	0.04	0.37	<0.01	0.08	<0.01	0.57	0.040	0.338	0.013	0.69	1.51	N.A.
646671	Drill Core	0.52	<0.01	0.194	24.58	0.03	0.24	<0.01	0.02	<0.01	0.48	0.044	0.174	0.010	0.61	1.74	N.A.
646672	Drill Core	1.77	<0.01	0.175	24.14	0.04	0.20	0.01	<0.01	<0.01	0.30	0.013	0.116	0.008	0.38	1.15	3.16
646673	Drill Core	2.69	<0.01	0.165	22.34	0.06	0.31	0.03	0.06	<0.01	0.71	0.031	0.182	0.011	0.62	1.52	N.A.
646674	Drill Core	1.68	<0.01	0.241	21.74	0.03	0.22	0.01	<0.01	<0.01	2.80	0.207	0.533	0.033	1.54	1.20	N.A.
646675	Rock Pulp	1.19	<0.01	0.182	20.96	0.02	0.29	0.03	0.08	<0.01	3.17	0.049	0.411	0.026	1.40	2.02	N.A.
646676	Rock Pulp	4.30	0.01	1.007	13.19	0.19	3.98	0.31	0.10	<0.01	0.50	0.055	0.192	0.007	0.41	0.39	N.A.
646677	Drill Core	1.28	<0.01	0.177	24.66	0.02	0.18	0.01	<0.01	<0.01	1.17	0.049	0.254	0.015	0.92	1.81	N.A.
646678	Drill Core	0.25	<0.01	0.130	26.70	0.02	0.17	<0.01	0.03	<0.01	0.22	0.005	0.199	0.008	0.48	2.02	N.A.
646679	Drill Core	0.93	<0.01	0.157	25.56	0.04	0.32	<0.01	0.07	<0.01	0.12	0.004	0.106	0.005	0.43	1.90	N.A.
646680	Drill Core	1.89	0.02	0.002	0.26	0.06	6.76	3.49	1.13	<0.01	<0.01	<0.001	0.002	<0.001	0.07	0.05	N.A.
646681	Drill Core	0.88	<0.01	0.191	26.00	0.04	0.35	0.01	0.08	<0.01	0.12	0.011	0.105	0.005	0.46	1.87	N.A.
646682	Drill Core	1.02	<0.01	0.204	25.74	0.04	0.35	0.02	0.05	<0.01	0.14	0.006	0.134	0.007	0.64	2.93	N.A.
646683	Drill Core	0.73	<0.01	0.214	25.32	0.03	0.32	<0.01	<0.01	<0.01	0.16	0.010	0.142	0.007	0.63	3.04	N.A.
646684	Drill Core	1.12	<0.01	0.229	25.55	0.03	0.25	<0.01	<0.01	<0.01	0.22	0.023	0.136	0.007	0.56	2.69	N.A.
646685	Drill Core	0.93	<0.01	0.187	25.79	0.03	0.26	<0.01	0.01	<0.01	0.34	0.014	0.163	0.006	0.98	3.58	N.A.
646686	Drill Core	1.73	<0.01	0.179	24.44	0.03	0.28	0.02	<0.01	<0.01	0.49	0.021	0.204	0.008	0.85	2.36	N.A.
646687	Drill Core	1.96	<0.01	0.130	22.11	0.03	0.33	0.01	<0.01	<0.01	0.70	0.031	0.247	0.012	0.87	2.64	N.A.
646688	Drill Core	1.79	0.02	0.083	20.66	0.06	0.64	<0.01	<0.01	<0.01	0.72	0.067	0.250	0.016	0.65	1.55	N.A.
646689	Drill Core	2.98	0.03	0.090	16.20	0.09	2.16	0.69	0.55	<0.01	1.35	0.114	0.213	0.019	0.93	1.11	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 05, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000699.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646690	Drill Core	6.19	<2	8	11	0.09	<0.001	0.004	<0.02	<0.01	<2	0.072	0.006	0.18	7.44	<0.02	0.06	<0.001	<0.01	<0.01	0.02
646691	Drill Core	5.95	2	18	6	0.66	<0.001	0.093	<0.02	<0.01	<2	0.065	0.019	0.14	8.04	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646692	Drill Core	8.62	<2	9	8	0.92	<0.001	0.171	<0.02	<0.01	<2	0.174	0.019	0.12	9.07	<0.02	0.03	<0.001	<0.01	<0.01	<0.01
646693	Drill Core	8.85	14	28	32	0.76	<0.001	0.106	<0.02	<0.01	<2	0.231	0.017	0.13	8.35	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646694	Drill Core	8.53	8	108	114	0.33	<0.001	0.051	<0.02	<0.01	<2	0.224	0.014	0.13	8.10	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646695	Drill Core	8.98	6	106	89	1.75	<0.001	0.168	<0.02	<0.01	<2	0.550	0.025	0.14	10.23	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646696	Drill Core	9.35	5	116	143	1.30	<0.001	0.125	<0.02	<0.01	2	0.463	0.020	0.13	8.89	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646697	Drill Core	10.48	5	55	70	0.51	<0.001	0.080	<0.02	<0.01	<2	0.313	0.015	0.14	8.16	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646698	Drill Core	10.66	8	53	73	0.53	<0.001	0.070	<0.02	<0.01	<2	0.295	0.016	0.14	8.69	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646699	Drill Core	8.75	4	14	16	0.86	<0.001	0.034	<0.02	<0.01	<2	0.121	0.009	0.15	7.67	<0.02	0.08	<0.001	<0.01	<0.01	0.01
646700	Rock Pulp	0.02	I.S.	I.S.	I.S.	0.46	<0.001	0.056	<0.02	0.02	<2	0.230	0.011	0.11	9.27	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646701	Rock Pulp	0.02	I.S.	I.S.	I.S.	1.40	<0.001	0.031	<0.02	<0.01	<2	0.258	0.017	0.12	9.33	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646702	Drill Core	8.99	<2	30	33	1.18	<0.001	0.036	<0.02	<0.01	<2	0.210	0.013	0.13	8.63	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646703	Drill Core	9.73	2	12	9	0.85	<0.001	0.012	<0.02	<0.01	<2	0.104	0.007	0.15	7.83	<0.02	0.02	<0.001	<0.01	<0.01	0.03
646704	Drill Core	6.57	3	9	10	1.11	<0.001	0.020	<0.02	<0.01	<2	0.168	0.012	0.15	8.97	<0.02	<0.01	<0.001	<0.01	<0.01	0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 05, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000699.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
646690	Drill Core	8.22	0.10	0.058	9.68	0.29	5.90	0.30	1.68	<0.01	0.12	0.004	0.050	0.002	0.20	0.21	N.A.
646691	Drill Core	2.16	0.03	0.109	18.53	0.09	2.35	0.01	0.24	<0.01	0.56	0.087	0.065	0.016	0.47	0.87	N.A.
646692	Drill Core	2.42	0.03	0.139	18.77	0.08	1.82	0.02	0.42	<0.01	0.77	0.147	0.164	0.016	0.65	0.74	2.87
646693	Drill Core	1.45	0.01	0.130	22.03	0.04	0.66	0.11	0.10	<0.01	0.68	0.111	0.209	0.015	0.89	2.38	N.A.
646694	Drill Core	0.72	<0.01	0.174	23.48	0.02	0.18	<0.01	0.01	<0.01	0.33	0.053	0.188	0.011	0.67	2.75	N.A.
646695	Drill Core	0.84	<0.01	0.156	24.43	0.02	0.15	<0.01	0.05	<0.01	0.83	0.160	0.492	0.023	1.43	2.26	N.A.
646696	Drill Core	1.20	<0.01	0.210	21.59	0.06	1.25	0.51	0.18	<0.01	1.11	0.181	0.388	0.022	1.99	1.68	N.A.
646697	Drill Core	0.95	<0.01	0.198	24.29	0.05	1.06	0.49	0.14	<0.01	0.50	0.081	0.228	0.010	0.98	2.65	N.A.
646698	Drill Core	0.66	<0.01	0.217	25.88	0.02	0.11	<0.01	<0.01	<0.01	0.49	0.068	0.207	0.010	1.04	3.21	N.A.
646699	Drill Core	4.33	0.07	0.108	13.43	0.23	4.36	0.95	1.53	<0.01	0.84	0.036	0.106	0.007	0.78	1.10	N.A.
646700	Rock Pulp	4.39	<0.01	1.087	14.12	0.20	4.18	0.32	0.11	<0.01	0.50	0.057	0.188	0.008	0.64	0.61	N.A.
646701	Rock Pulp	0.72	<0.01	0.140	25.10	0.02	0.31	<0.01	0.07	<0.01	1.14	0.031	0.230	0.015	1.27	3.86	N.A.
646702	Drill Core	1.73	0.02	0.145	20.26	0.07	0.99	0.06	0.50	<0.01	1.17	0.035	0.182	0.012	1.12	2.01	N.A.
646703	Drill Core	4.25	0.03	0.088	15.11	0.13	2.17	0.95	0.59	<0.01	0.80	0.014	0.097	0.007	0.78	0.79	N.A.
646704	Drill Core	2.12	<0.01	0.170	21.13	0.03	0.18	0.03	0.01	<0.01	1.09	0.018	0.138	0.011	1.41	3.24	N.A.

QUALITY CONTROL REPORT

SMI08000699.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
Pulp Duplicates																					
646661	Drill Core	10.38	<2	4	6	0.13	<0.001	0.002	<0.02	<0.01	<2	0.215	0.013	0.14	7.86	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646661	QC						<0.001	0.002	<0.02	<0.01	<2	0.211	0.013	0.14	7.90	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646667	Drill Core	11.56	9	28	82	11.20	<0.001	0.323	<0.02	<0.01	<2	1.117	0.071	0.13	22.62	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646667	QC		6	30	70																
REP 646671	QC																				
646673	Drill Core	9.87	<2	8	10	0.76	<0.001	0.030	<0.02	<0.01	<2	0.204	0.016	0.12	8.22	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646673	QC					0.77															
646683	Drill Core	10.23	<2	14	14	0.16	<0.001	0.011	<0.02	<0.01	<2	0.216	0.013	0.11	7.64	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646683	QC																				
646699	Drill Core	8.75	4	14	16	0.86	<0.001	0.034	<0.02	<0.01	<2	0.121	0.009	0.15	7.67	<0.02	0.08	<0.001	<0.01	<0.01	0.01
REP 646699	QC		3	16	18																
Core Reject Duplicates																					
646671	Drill Core	10.18	3	3	9	0.55	<0.001	0.044	<0.02	<0.01	<2	0.206	0.015	0.13	8.15	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
DUP 646671	QC		<2	3	8	0.52	<0.001	0.044	<0.02	<0.01	<2	0.210	0.015	0.13	8.26	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
Reference Materials																					
STD CDN-PGMS-14	Standard		261	113	419																
STD CDN-PGMS-14	Standard		250	111	417																
STD CDN-PGMS-14	Standard		230	112	413																
STD CSC	Standard					4.29															
STD CSC	Standard					4.28															
STD CSC	Standard					4.24															
STD FA10R	Standard		477	462	475																
STD FA10R	Standard		458	448	457																
STD FA10R	Standard		486	475	486																
STD OREAS76A	Standard					18.26															
STD OREAS76A	Standard					17.35															
STD OREAS76A	Standard					17.02															
STD R3NI	Standard																				

QUALITY CONTROL REPORT

SMI08000699.1

Method		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
Unit		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
Pulp Duplicates																	
646661	Drill Core	0.34	<0.01	0.210	24.59	0.03	0.32	<0.01	0.07	<0.01	0.20	0.003	0.125	0.007	0.39	1.70	N.A.
REP 646661	QC	0.33	<0.01	0.194	24.67	0.03	0.31	<0.01	0.07	<0.01	0.13						
646667	Drill Core	0.10	<0.01	0.161	18.12	0.02	0.15	<0.01	<0.01	<0.01	7.95	0.319	1.156	0.074	4.37	1.54	N.A.
REP 646667	QC											0.045	0.176	0.010	0.62	1.83	
646673	Drill Core	2.69	<0.01	0.165	22.34	0.06	0.31	0.03	0.06	<0.01	0.71	0.031	0.182	0.011	0.62	1.52	N.A.
REP 646673	QC											0.010	0.141	0.007	0.64	3.13	
646683	Drill Core	0.73	<0.01	0.214	25.32	0.03	0.32	<0.01	<0.01	<0.01	0.16	0.010	0.142	0.007	0.63	3.04	N.A.
REP 646683	QC											0.010	0.141	0.007	0.64	3.13	
646699	Drill Core	4.33	0.07	0.108	13.43	0.23	4.36	0.95	1.53	<0.01	0.84	0.036	0.106	0.007	0.78	1.10	N.A.
REP 646699	QC											0.036	0.103	0.007	0.74	1.06	
Core Reject Duplicates																	
646671	Drill Core	0.52	<0.01	0.194	24.58	0.03	0.24	<0.01	0.02	<0.01	0.48	0.044	0.174	0.010	0.61	1.74	N.A.
DUP 646671	QC	0.52	<0.01	0.192	24.66	0.03	0.25	<0.01	0.02	<0.01	0.49	0.045	0.185	0.010	0.67	2.06	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard																
STD CSC	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																
STD OREAS76A	Standard																
STD OREAS76A	Standard																
STD R3NI	Standard											0.767	0.410	0.056	4.74	0.17	

QUALITY CONTROL REPORT

SMI08000699.1

		WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
STD R3NI	Standard																				
STD R3NI	Standard																				
STD R3T	Standard					0.079	0.820	2.03	4.12	218	0.547	0.064	0.09	32.98	0.02	<0.01	0.024	0.04	<0.01	0.02	
STD R3T	Standard					0.078	0.817	2.04	4.10	213	0.546	0.065	0.09	33.04	0.02	<0.01	0.025	0.04	<0.01	0.02	
STD R3T	Standard					0.077	0.828	2.06	4.27	208	0.550	0.063	0.10	33.42	0.03	<0.01	0.024	0.03	<0.01	0.02	
STD R3T	Standard					0.077	0.838	2.06	4.26	199	0.553	0.063	0.10	33.60	0.03	<0.01	0.024	0.03	<0.01	0.02	
STD R3T Expected						0.077	0.805	1.98	4.1	190	0.525	0.061	0.09	34.17	0.04	0.01	0.024	0.04			
STD FA10R Expected			485	472	476																
STD CDN-PGMS-14			259	119	451																
STD R3NI Expected																					
STD CSC Expected						4.19															
STD OREAS76A Expected						18															
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank					<0.02															
BLK	Blank					<0.02															
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank																				
BLK	Blank					<0.02															
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.24	<0.02	0.07	<0.001	<0.01	<0.01	<0.01

QUALITY CONTROL REPORT

SMI08000699.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
STD R3NI	Standard											0.507	0.446	0.055	6.18	0.62	
STD R3NI	Standard											0.715	0.405	0.054	5.45	0.14	
STD R3T	Standard	2.28	0.07	0.021	1.69	0.18	2.45	0.32	0.59	<0.01	16.51						
STD R3T	Standard	2.28	0.07	0.021	1.69	0.18	2.45	0.32	0.59	<0.01	16.54						
STD R3T	Standard	2.28	0.05	0.022	1.70	0.18	2.51	0.32	0.60	<0.01	16.87						
STD R3T	Standard	2.29	0.05	0.022	1.72	0.19	2.51	0.32	0.60	<0.01	16.82						
STD R3T Expected		2.23	0.05	0.02	1.64		2.44	0.31	0.59								
STD FA10R Expected																	
STD CDN-PGMS-14																	
STD R3NI Expected												0.42					
STD CSC Expected																	
STD OREAS76A Expected																	
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank																
Prep Wash																	
G1	Prep Blank	2.34	0.07	0.002	0.68	0.23	7.42	2.69	2.91	<0.01	<0.01	<0.001	<0.001	<0.001	0.14	0.06	N.A.

QUALITY CONTROL REPORT

SMI08000699.1

		WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
G1	Prep Blank	<0.01	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.13	<0.02	0.07	<0.001	<0.01	<0.01	<0.01

QUALITY CONTROL REPORT

SMI08000699.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NIS	8NIS	8NIS	8NIS	8NIS	G8SG	
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.001	0.01	0.01	0
G1	Prep Blank	2.35	0.07	0.001	0.62	0.22	7.48	2.69	2.82	<0.01	<0.01	<0.001	<0.001	<0.001	0.09	0.03	N.A.

Hole 08-257



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Email Distribution List
 Receiving Lab: Canada-Smithers
 Received: August 11, 2008
 Report Date: October 14, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000725.1

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-257A
 P.O. Number
 Number of Samples: 44

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC: Email Distribution List

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	42	Crush split and pulverize drill core to 200 mesh		
3B	44	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
7TD	44	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	44	Leached with H2O2 + NH4 citrate	1	Completed
2A (Total S)	44	Analysis by Leco	0.1	Completed
Specific Gravity	3	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. ** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 14, 2008

Page: 2 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000725.1

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646705	Drill Core	6.76	<2	16	27	<0.001	0.020	<0.02	0.01	<2	0.278	0.015	0.17	9.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.58
646706	Drill Core	10.68	<2	6	10	<0.001	0.024	<0.02	<0.01	<2	0.219	0.012	0.15	9.07	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	2.77
646707	Drill Core	11.15	<2	<3	10	<0.001	0.012	<0.02	0.01	<2	0.225	0.013	0.16	9.27	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.54
646708	Drill Core	11.25	<2	3	11	<0.001	0.020	<0.02	<0.01	<2	0.219	0.014	0.15	9.19	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	3.10
646709	Drill Core	10.86	<2	<3	17	<0.001	0.023	<0.02	<0.01	<2	0.253	0.015	0.15	9.29	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.62
646710	Drill Core	1.27	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	0.002	<0.001	0.08	1.12	<0.02	0.08	<0.001	<0.01	<0.01	<0.01	2.13
646711	Drill Core	10.90	<2	8	12	<0.001	0.012	<0.02	0.01	<2	0.224	0.013	0.15	9.09	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.61
646712	Drill Core	10.71	<2	7	10	<0.001	0.021	<0.02	<0.01	<2	0.205	0.014	0.15	9.36	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.36
646713	Drill Core	9.70	<2	4	4	<0.001	0.012	<0.02	<0.01	<2	0.212	0.012	0.17	9.73	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.42
646714	Drill Core	8.82	<2	4	4	<0.001	0.011	<0.02	<0.01	<2	0.082	0.007	0.14	6.77	<0.02	0.07	<0.001	<0.01	<0.01	0.02	5.16
646715	Drill Core	9.10	<2	<3	4	<0.001	0.014	<0.02	<0.01	<2	0.062	0.008	0.14	7.79	<0.02	0.06	<0.001	<0.01	<0.01	0.02	5.45
646716	Drill Core	10.37	<2	<3	7	<0.001	0.027	<0.02	<0.01	<2	0.132	0.011	0.14	9.32	<0.02	<0.01	<0.001	<0.01	<0.01	0.03	5.47
646717	Drill Core	10.53	<2	23	17	<0.001	0.020	<0.02	0.01	<2	0.222	0.015	0.15	9.81	<0.02	<0.01	<0.001	<0.01	<0.01	0.01	2.69
646718	Drill Core	10.40	<2	26	21	<0.001	0.007	<0.02	<0.01	<2	0.265	0.013	0.15	8.52	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.70
646719	Drill Core	10.11	<2	<3	7	<0.001	0.011	<0.02	<0.01	<2	0.256	0.013	0.16	9.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.28
646720	Drill Core	11.21	<2	10	8	<0.001	0.015	<0.02	0.01	<2	0.241	0.014	0.15	9.12	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.92
646721	Drill Core	10.60	<2	30	36	<0.001	0.018	<0.02	0.01	<2	0.278	0.017	0.15	9.72	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.49
646722	Drill Core	9.91	<2	8	7	<0.001	0.008	<0.02	<0.01	<2	0.225	0.012	0.15	8.77	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.42
646723	Drill Core	11.68	<2	13	11	<0.001	0.009	<0.02	<0.01	<2	0.223	0.013	0.14	8.30	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.51
646724	Drill Core	11.14	<2	18	16	<0.001	0.019	<0.02	<0.01	<2	0.207	0.014	0.15	8.76	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.61
646725	Drill Core	0.03	I.S.	I.S.	I.S.	<0.001	0.058	<0.02	0.02	<2	0.250	0.012	0.12	9.07	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	4.42
646726	Drill Core	0.02	I.S.	I.S.	I.S.	<0.001	0.031	<0.02	<0.01	<2	0.264	0.017	0.12	8.80	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.71
646727	Drill Core	8.92	<2	34	27	<0.001	0.018	<0.02	<0.01	<2	0.207	0.012	0.14	7.63	<0.02	0.02	<0.001	<0.01	<0.01	<0.01	3.42
646728	Drill Core	8.87	<2	10	9	<0.001	0.013	<0.02	<0.01	<2	0.088	0.006	0.14	6.93	<0.02	0.11	<0.001	<0.01	<0.01	0.02	6.27
646729	Drill Core	8.97	<2	7	7	<0.001	0.018	<0.02	<0.01	<2	0.193	0.011	0.13	8.51	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.10
646730A	Drill Core	11.98	<2	11	11	<0.001	0.012	<0.02	0.01	<2	0.234	0.014	0.15	8.48	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.86
646730B	Drill Core		<2	12	9	<0.001	0.011	<0.02	<0.01	<2	0.228	0.013	0.14	8.26	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.76
646731	Drill Core	10.56	4	84	79	<0.001	0.026	<0.02	0.01	<2	0.266	0.016	0.15	9.27	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.81
646732	Drill Core	10.94	5	30	26	<0.001	0.046	<0.02	<0.01	<2	0.237	0.016	0.15	8.89	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.14
646733	Drill Core	11.13	4	22	17	<0.001	0.042	<0.02	<0.01	<2	0.251	0.017	0.15	9.16	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.16



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

ACME ANALYTICAL LABORATORIES LTD.

www.acmelab.com

Client:

Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project:

Turnagain

Report Date:

October 14, 2008

Page:

2 of 3

Part 2

CERTIFICATE OF ANALYSIS

SMI08000725.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS 2A	Leco	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0	
646705	Drill Core	<0.01	0.145	24.93	0.02	0.11	0.02	<0.01	<0.01	0.77	0.020	0.201	0.008	1.46	2.81	0.83	N.A.
646706	Drill Core	<0.01	0.151	23.20	0.05	0.28	0.03	<0.01	<0.01	0.70	0.022	0.143	0.007	1.24	2.48	0.69	N.A.
646707	Drill Core	<0.01	0.205	24.22	0.02	0.09	0.02	<0.01	<0.01	0.56	0.022	0.184	0.009	1.47	3.04	0.59	N.A.
646708	Drill Core	<0.01	0.148	21.94	0.03	0.14	0.03	<0.01	<0.01	0.91	0.001	0.002	<0.001	0.11	0.08	0.98	N.A.
646709	Drill Core	<0.01	0.159	23.43	0.02	0.12	0.02	<0.01	<0.01	0.90	0.011	0.137	0.006	1.17	2.76	0.94	N.A.
646710	Drill Core	0.01	0.003	0.34	0.07	8.36	3.64	1.21	<0.01	0.01	0.019	0.166	0.008	1.36	2.66	0.02	N.A.
646711	Drill Core	<0.01	0.115	24.02	0.02	0.10	0.02	<0.01	<0.01	0.58	0.012	0.141	0.007	1.28	3.29	0.57	N.A.
646712	Drill Core	<0.01	0.143	22.65	0.02	0.12	0.03	<0.01	<0.01	0.97	0.020	0.149	0.008	1.25	2.82	1.04	3.14
646713	Drill Core	<0.01	0.155	22.58	0.04	0.18	0.02	<0.01	<0.01	0.76	0.012	0.151	0.007	1.28	2.94	0.81	N.A.
646714	Drill Core	0.08	0.072	10.85	0.23	5.48	1.71	1.27	<0.01	0.58	0.012	0.069	0.005	0.45	0.52	0.52	N.A.
646715	Drill Core	0.08	0.089	9.72	0.24	5.16	1.58	1.35	<0.01	0.81	0.014	0.053	0.005	0.52	0.43	0.82	N.A.
646716	Drill Core	<0.01	0.142	18.36	0.07	0.38	0.04	<0.01	<0.01	1.02	0.025	0.113	0.009	0.89	1.66	1.14	N.A.
646717	Drill Core	<0.01	0.135	22.27	0.04	0.22	0.03	<0.01	<0.01	0.85	0.019	0.184	0.010	1.21	2.73	0.89	N.A.
646718	Drill Core	<0.01	0.104	26.19	0.02	0.10	0.02	<0.01	<0.01	0.30	0.008	0.138	0.006	0.92	2.94	0.29	N.A.
646719	Drill Core	<0.01	0.160	25.06	0.02	0.10	0.01	<0.01	<0.01	0.47	0.011	0.175	0.007	1.11	3.19	0.45	N.A.
646720	Drill Core	<0.01	0.124	24.26	0.02	0.11	0.02	<0.01	<0.01	0.47	0.015	0.153	0.007	1.08	2.92	0.49	N.A.
646721	Drill Core	<0.01	0.136	22.00	0.03	0.29	0.02	<0.01	<0.01	0.99	0.017	0.238	0.012	1.16	2.57	1.05	N.A.
646722	Drill Core	<0.01	0.157	22.96	0.03	0.16	0.03	<0.01	<0.01	0.57	0.008	0.141	0.006	1.17	2.74	0.58	3.06
646723	Drill Core	<0.01	0.151	23.25	0.03	0.17	0.03	<0.01	<0.01	0.51	0.009	0.132	0.006	1.13	2.74	0.50	N.A.
646724	Drill Core	<0.01	0.136	22.14	0.02	0.12	0.03	<0.01	<0.01	0.65	0.019	0.141	0.008	1.30	2.99	0.70	N.A.
646725	Drill Core	<0.01	1.139	13.45	0.19	4.13	0.33	0.12	<0.01	0.52	0.060	0.210	0.008	0.56	0.54	0.48	N.A.
646726	Drill Core	<0.01	0.132	23.41	0.02	0.32	<0.01	0.08	<0.01	1.20	0.030	0.241	0.013	1.23	3.39	1.36	N.A.
646727	Drill Core	<0.01	0.070	20.11	0.05	0.96	0.14	0.13	<0.01	0.55	0.018	0.151	0.007	1.14	2.93	0.50	N.A.
646728	Drill Core	0.09	0.074	9.96	0.26	5.73	1.00	1.63	<0.01	0.19	0.013	0.071	0.004	0.35	0.80	0.18	N.A.
646729	Drill Core	<0.01	0.106	20.70	0.02	0.18	0.02	<0.01	<0.01	0.38	0.018	0.155	0.008	0.81	2.53	0.40	N.A.
646730A	Drill Core	<0.01	0.101	23.49	0.03	0.14	0.03	<0.01	<0.01	0.31	0.013	0.137	0.006	0.94	2.55	0.32	N.A.
646730B	Drill Core	<0.01	0.102	22.96	0.03	0.13	0.03	<0.01	<0.01	0.31	0.012	0.131	0.006	0.93	2.59	0.31	N.A.
646731	Drill Core	<0.01	0.169	24.29	0.03	0.13	0.02	<0.01	<0.01	0.41	0.025	0.173	0.008	1.04	2.72	0.41	N.A.
646732	Drill Core	<0.01	0.159	24.16	0.02	0.09	0.01	<0.01	<0.01	0.44	0.049	0.147	0.007	1.15	2.96	0.43	3.20
646733	Drill Core	<0.01	0.200	24.67	0.02	0.09	0.01	<0.01	<0.01	0.52	0.043	0.163	0.008	1.27	3.14	0.55	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 14, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000725.1

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
646734	Drill Core	10.69	<2	35	32	<0.001	0.051	<0.02	0.01	<2	0.318	0.017	0.15	9.22	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.89
646735	Drill Core	11.06	6	33	38	<0.001	0.051	<0.02	<0.01	<2	0.363	0.019	0.14	9.79	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.99
646736	Drill Core	10.44	<2	25	25	<0.001	0.035	<0.02	<0.01	<2	0.218	0.015	0.14	8.31	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.81
646737	Drill Core	10.00	<2	18	22	<0.001	0.014	<0.02	0.01	<2	0.203	0.014	0.14	8.60	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.32
646738	Drill Core	10.47	<2	21	18	<0.001	0.034	<0.02	0.01	<2	0.241	0.015	0.14	8.19	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.80
646739	Drill Core	9.46	<2	54	37	<0.001	0.026	<0.02	<0.01	<2	0.217	0.015	0.13	8.18	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.79
646740	Drill Core	2.01	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	0.001	<0.001	0.08	1.20	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.17
646741	Drill Core	10.63	4	16	31	<0.001	0.017	<0.02	<0.01	<2	0.242	0.013	0.13	8.02	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.44
646742	Drill Core	11.06	<2	10	13	<0.001	0.010	<0.02	<0.01	<2	0.192	0.012	0.12	7.37	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.53
646743	Drill Core	10.75	2	7	12	<0.001	0.006	<0.02	<0.01	<2	0.202	0.012	0.13	7.68	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.07
646744	Drill Core	11.02	<2	13	17	<0.001	0.027	<0.02	<0.01	<2	0.203	0.014	0.12	7.46	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.85
646745	Drill Core	11.47	<2	9	7	<0.001	0.002	<0.02	<0.01	<2	0.229	0.013	0.11	6.47	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.63
646746	Drill Core	11.12	<2	9	11	<0.001	0.004	<0.02	<0.01	<2	0.267	0.013	0.12	7.00	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.66
646747	Drill Core	10.90	<2	8	20	<0.001	0.007	<0.02	<0.01	<2	0.270	0.014	0.13	7.84	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.78



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 14, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000725.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS 2A	Leco	G8SG
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	TOT/S	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0	
646734	Drill Core	<0.01	0.263	24.70	0.02	0.11	<0.01	<0.01	<0.01	0.58	0.051	0.227	0.009	1.34	3.25	0.59	N.A.
646735	Drill Core	<0.01	0.173	24.71	0.02	0.12	0.01	<0.01	<0.01	0.80	0.053	0.290	0.011	1.44	3.12	0.84	N.A.
646736	Drill Core	<0.01	0.179	23.74	0.02	0.09	<0.01	<0.01	<0.01	0.46	0.037	0.139	0.007	1.07	2.67	0.51	N.A.
646737	Drill Core	0.01	0.185	25.60	0.03	0.13	0.02	<0.01	<0.01	0.28	0.010	0.074	0.004	0.34	1.06	0.21	N.A.
646738	Drill Core	<0.01	0.202	25.37	0.02	0.13	0.01	<0.01	<0.01	0.47	0.029	0.146	0.007	0.74	2.37	0.43	N.A.
646739	Drill Core	<0.01	0.150	24.31	0.02	0.15	0.02	<0.01	<0.01	0.41	0.022	0.109	0.006	0.69	2.01	0.42	N.A.
646740	Drill Core	0.03	<0.001	0.31	0.08	8.18	3.70	1.19	<0.01	<0.01	<0.001	0.001	<0.001	0.05	0.03	<0.02	N.A.
646741	Drill Core	<0.01	0.108	25.16	0.03	0.15	0.02	<0.01	<0.01	0.42	0.015	0.129	0.005	0.63	1.69	0.42	N.A.
646742	Drill Core	<0.01	0.121	22.97	0.03	0.17	0.04	<0.01	<0.01	0.35	0.009	0.108	0.005	0.57	1.72	0.34	N.A.
646743	Drill Core	<0.01	0.111	24.12	0.03	0.16	0.03	<0.01	<0.01	0.19	0.011	0.077	0.004	0.56	1.55	0.16	N.A.
646744	Drill Core	<0.01	0.141	25.64	0.01	0.11	0.01	<0.01	<0.01	0.16	0.024	0.076	0.005	0.56	2.31	0.15	N.A.
646745	Drill Core	<0.01	0.155	27.13	0.01	0.11	0.01	0.01	<0.01	0.03	0.002	0.034	0.003	0.58	1.96	0.02	N.A.
646746	Drill Core	<0.01	0.227	26.65	0.01	0.12	0.01	<0.01	<0.01	0.04	0.004	0.048	0.003	0.55	1.90	0.07	N.A.
646747	Drill Core	<0.01	0.238	26.06	0.01	0.12	0.01	0.01	<0.01	0.10	0.007	0.071	0.003	0.63	1.74	0.11	N.A.

QUALITY CONTROL REPORT

SMI08000725.1

Method	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
Pulp Duplicates																					
646714	Drill Core	8.82	<2	4	4	<0.001	0.011	<0.02	<0.01	<2	0.082	0.007	0.14	6.77	<0.02	0.07	<0.001	<0.01	<0.01	0.02	5.16
REP 646714	QC																				
646719	Drill Core	10.11	<2	<3	7	<0.001	0.011	<0.02	<0.01	<2	0.256	0.013	0.16	9.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.28
REP 646719	QC					<0.001	0.010	<0.02	<0.01	<2	0.251	0.013	0.15	9.77	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	1.27
REP 646721	QC																				
646742	Drill Core	11.06	<2	10	13	<0.001	0.010	<0.02	<0.01	<2	0.192	0.012	0.12	7.37	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	3.53
REP 646742	QC																				
Core Reject Duplicates																					
646721	Drill Core	10.60	<2	30	36	<0.001	0.018	<0.02	0.01	<2	0.278	0.017	0.15	9.72	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.49
DUP 646721	QC		<2	38	41	<0.001	0.018	<0.02	<0.01	<2	0.279	0.017	0.15	9.95	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	2.46
Reference Materials																					
STD CDN-PGMS-14	Standard		241	124	439																
STD CDN-PGMS-14	Standard		291	123	448																
STD CSC	Standard																				
STD CSC	Standard																				
STD FA10R	Standard		476	458	475																
STD FA10R	Standard		478	427	466																
STD FA10R	Standard		450	446	464																
STD FA10R	Standard		466	460	481																
STD OREAS76A	Standard																				
STD OREAS76A	Standard																				
STD R3NI	Standard																				
STD R4T	Standard					0.063	0.521	1.60	3.54	89	0.368	0.044	0.09	24.95	<0.02	0.02	0.020	0.02	<0.01	0.02	2.27
STD R4T	Standard					0.062	0.514	1.54	3.46	86	0.356	0.041	0.09	24.29	<0.02	0.02	0.018	0.02	<0.01	0.02	2.19
STD SF-3A_NI	Standard																				
STD SF-3A_NI	Standard																				
STD SF-3T	Standard					0.032	0.764	0.96	1.07	54	0.355	0.019	0.44	8.40	<0.02	0.04	0.005	<0.01	<0.01	0.01	4.16
STD SF-3T	Standard					0.031	0.786	0.94	1.10	52	0.352	0.018	0.44	8.47	<0.02	0.04	0.004	<0.01	<0.01	0.01	4.08

QUALITY CONTROL REPORT

SMI08000725.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS 2A Leco	G8SG	
Analyte	P	Cr	Mg	Ti	Al	Na	K	W	S		Cu	Ni	Co	Fe	Mg	TOT/S	SG
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
MDL	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	0
Pulp Duplicates																	
646714	Drill Core	0.08	0.072	10.85	0.23	5.48	1.71	1.27	<0.01	0.58	0.012	0.069	0.005	0.45	0.52	0.52	N.A.
REP 646714	QC										0.012	0.069	0.004	0.43	0.49		
646719	Drill Core	<0.01	0.160	25.06	0.02	0.10	0.01	<0.01	<0.01	0.47	0.011	0.175	0.007	1.11	3.19	0.45	N.A.
REP 646719	QC	<0.01	0.158	24.67	0.02	0.10	0.02	<0.01	<0.01	0.47						0.46	
REP 646721	QC										0.017	0.233	0.012	1.19	2.63		
646742	Drill Core	<0.01	0.121	22.97	0.03	0.17	0.04	<0.01	<0.01	0.35	0.009	0.108	0.005	0.57	1.72	0.34	N.A.
REP 646742	QC										0.009	0.108	0.005	0.59	1.74		
Core Reject Duplicates																	
646721	Drill Core	<0.01	0.136	22.00	0.03	0.29	0.02	<0.01	<0.01	0.99	0.017	0.238	0.012	1.16	2.57	1.05	N.A.
DUP 646721	QC	<0.01	0.134	21.56	0.03	0.29	0.02	<0.01	<0.01	0.98	0.017	0.246	0.012	1.34	2.94	1.08	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard															4.27	
STD CSC	Standard															4.10	
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard															17.47	
STD OREAS76A	Standard															17.21	
STD R3NI	Standard										0.757	0.403	0.052	3.60	0.14		
STD R4T	Standard	0.05	0.019	1.51	0.21	4.04	0.97	1.19	<0.01	12.22							
STD R4T	Standard	0.05	0.018	1.41	0.20	3.96	0.91	1.18	<0.01	12.28							
STD SF-3A_NI	Standard										0.803	0.331	0.016	1.88	2.66		
STD SF-3A_NI	Standard										0.793	0.328	0.015	1.59	2.24		
STD SF-3T	Standard	0.06	0.022	4.84	0.21	5.48	2.06	2.50	<0.01	4.29							
STD SF-3T	Standard	0.06	0.016	4.63	0.20	5.44	2.10	2.46	<0.01	4.14							

QUALITY CONTROL REPORT

SMI08000725.1

	WGHT	3B	3B	3B	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	Ca	
	kg	ppb	ppb	ppb	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	%	
	0.01	2	3	2	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	0.01	
STD CSC Expected																					
STD OREAS76A Expected																					
STD SF-3T Expected					0.032	0.7723	0.961	1.0672	52	0.35	0.0181	0.432	8.33	0.004	0.044	0.00475	0.00111	0.00048	0.0143	4.1	
STD R4T Expected					0.062	0.501	1.55	3.38	87	0.354	0.04	0.09	23.82	0.02	0.02	0.018	0.01	0.01	0.017	2.14	
STD R3NI Expected																					
STD CDN-PGMS-14		259	119	451																	
STD FA10R Expected		485	472	476																	
STD SF-3A_NI Expected																					
BLK	Blank				<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	
BLK	Blank				<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	
BLK	Blank				<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	
BLK	Blank																				
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.08	2.30	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	2.37
G1	Prep Blank	<0.01	<2	<3	<2	<0.001	<0.001	<0.02	<0.01	<2	0.001	<0.001	0.08	2.31	<0.02	0.08	<0.001	<0.01	<0.01	<0.01	2.59

QUALITY CONTROL REPORT

SMI08000725.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS 2A Leco	G8SG	
		P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg TOT/S	SG	
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0.02	
STD CSC Expected																4.19	
STD OREAS76A Expected																18	
STD SF-3T Expected		0.06	0.02074	4.67	0.19	5.43	2.06	2.47	0.00043	3.5							
STD R4T Expected		0.04	0.018	1.4		39	0.89	1.16	0.01								
STD R3NI Expected													0.42				
STD CDN-PGMS-14																	
STD FA10R Expected																	
STD SF-3A_NI Expected												0.3205					
BLK	Blank															<0.02	
BLK	Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01							
BLK	Blank															<0.02	
BLK	Blank	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01							
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank																
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank																
BLK	Blank																
BLK	Blank										<0.001	<0.001	<0.001	<0.01	<0.01		
Prep Wash																	
G1	Prep Blank	0.07	<0.001	0.67	0.24	7.85	2.55	2.98	<0.01	0.04	0.002	<0.001	<0.001	0.16	0.08	<0.02	N.A.
G1	Prep Blank	0.08	0.001	0.69	0.23	8.41	2.76	3.10	<0.01	0.02	0.002	<0.001	<0.001	0.12	0.04	0.02	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By:
 Receiving Lab: Canada-Smithers
 Received: August 14, 2008
 Report Date: September 12, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000748.1

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-257B
 P.O. Number
 Number of Samples: 35

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	31	Crush split and pulverize drill core to 200 mesh		
3B	35	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	35	Analysis by Leco	0.1	Completed
7TD	35	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	35	Leached with H2O2 + NH4 citrate	1	Completed
Specific Gravity	2	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 12, 2008

Page: 2 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000748.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646748	Drill Core	11.37	23	40	33	0.08	<0.001	0.005	<0.02	<0.01	<2	0.277	0.013	0.12	6.68	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646749	Drill Core	10.44	21	27	17	0.09	<0.001	0.004	<0.02	<0.01	<2	0.250	0.012	0.11	6.68	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646750	Rock Pulp	0.02	I.S.	I.S.	I.S.	4.12	0.001	0.048	<0.02	<0.01	<2	0.409	0.028	0.13	12.85	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646751	Rock Pulp	0.02	I.S.	I.S.	I.S.	0.47	<0.001	0.054	<0.02	0.01	<2	0.222	0.011	0.11	8.37	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646752	Drill Core	11.02	34	24	11	0.07	<0.001	0.003	<0.02	<0.01	<2	0.240	0.012	0.12	6.31	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646753	Drill Core	11.42	20	22	14	0.12	<0.001	0.008	<0.02	<0.01	<2	0.249	0.012	0.12	6.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646754	Drill Core	10.11	40	46	13	0.14	<0.001	0.009	<0.02	<0.01	<2	0.270	0.013	0.11	6.73	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646755	Drill Core	10.71	<2	51	52	0.31	<0.001	0.013	<0.02	<0.01	<2	0.281	0.014	0.12	7.54	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646756	Drill Core	11.42	<2	25	16	0.63	<0.001	0.017	<0.02	<0.01	<2	0.273	0.015	0.13	8.34	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646757	Drill Core	11.15	<2	17	18	0.69	<0.001	0.021	<0.02	<0.01	<2	0.280	0.017	0.12	8.39	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646758	Drill Core	9.23	<2	37	30	0.78	<0.001	0.019	<0.02	<0.01	<2	0.318	0.016	0.12	8.85	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646759	Drill Core	9.16	<2	33	30	0.36	<0.001	0.012	<0.02	<0.01	<2	0.273	0.014	0.13	8.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646760A	Drill Core	10.97	<2	56	45	0.35	<0.001	0.023	<0.02	<0.01	<2	0.333	0.016	0.12	8.35	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646760B	Drill Core		<2	58	47	0.35	<0.001	0.021	<0.02	<0.01	<2	0.327	0.016	0.12	8.35	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646761	Drill Core	10.13	<2	55	49	0.19	<0.001	0.009	<0.02	<0.01	<2	0.266	0.016	0.13	8.39	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646762	Drill Core	10.13	<2	25	20	0.12	<0.001	0.004	<0.02	<0.01	<2	0.270	0.013	0.12	7.63	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646763	Drill Core	11.04	<2	10	7	0.06	<0.001	0.001	<0.02	<0.01	<2	0.264	0.013	0.12	7.27	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646764	Drill Core	10.97	<2	15	9	0.05	<0.001	<0.001	<0.02	<0.01	<2	0.262	0.013	0.11	6.91	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646765	Drill Core	10.73	2	31	32	0.08	<0.001	0.001	<0.02	<0.01	<2	0.258	0.014	0.12	7.38	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646766	Drill Core	9.89	8	20	12	0.12	<0.001	0.001	<0.02	<0.01	<2	0.259	0.013	0.10	6.40	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646767	Drill Core	10.82	<2	15	8	0.10	<0.001	<0.001	<0.02	<0.01	<2	0.278	0.011	0.09	5.74	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646768	Drill Core	10.58	4	<3	11	0.12	<0.001	0.001	<0.02	<0.01	<2	0.278	0.011	0.10	6.25	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646769	Drill Core	10.12	10	16	7	0.16	<0.001	0.003	<0.02	<0.01	<2	0.250	0.011	0.12	6.34	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646770	Drill Core	1.02	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.002	<0.001	0.08	1.13	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
646771	Drill Core	9.82	<2	12	15	0.27	<0.001	0.006	<0.02	<0.01	<2	0.268	0.013	0.12	6.81	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646772	Drill Core	9.53	<2	6	24	0.45	<0.001	0.010	<0.02	<0.01	<2	0.252	0.015	0.12	7.18	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646773	Drill Core	9.26	<2	<3	7	0.63	<0.001	0.013	<0.02	<0.01	<2	0.156	0.010	0.08	7.34	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646774	Drill Core	10.12	<2	<3	7	0.78	0.001	0.009	<0.02	<0.01	<2	0.137	0.008	0.11	7.51	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646775	Rock Pulp	0.02	I.S.	I.S.	I.S.	1.42	<0.001	0.030	<0.02	<0.01	<2	0.261	0.017	0.12	8.86	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646776	Rock Pulp	0.02	I.S.	I.S.	I.S.	0.48	<0.001	0.056	<0.02	0.02	<2	0.238	0.011	0.11	8.65	<0.02	<0.01	<0.001	<0.01	<0.01	0.02



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 12, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000748.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
646748	Drill Core	0.54	<0.01	0.271	28.19	0.01	0.13	<0.01	0.01	<0.01	0.05	0.005	0.092	0.005	1.22	4.93	N.A.
646749	Drill Core	0.91	<0.01	0.223	26.66	0.02	0.19	<0.01	0.01	<0.01	0.09	0.003	0.120	0.006	1.18	4.83	N.A.
646750	Rock Pulp	1.19	<0.01	0.188	21.52	0.02	0.29	0.03	0.09	<0.01	3.02	0.004	0.380	0.026	2.82	3.24	N.A.
646751	Rock Pulp	4.24	<0.01	0.877	13.38	0.18	3.81	0.32	0.11	<0.01	0.45	0.056	0.184	0.008	0.59	0.67	N.A.
646752	Drill Core	1.06	<0.01	0.290	26.82	0.03	0.24	0.01	0.03	<0.01	0.06	0.003	0.091	0.005	1.10	4.92	3.21
646753	Drill Core	0.62	<0.01	0.268	27.26	0.02	0.16	<0.01	0.01	<0.01	0.10	0.005	0.112	0.006	1.12	4.76	N.A.
646754	Drill Core	0.49	<0.01	0.237	27.36	0.02	0.19	<0.01	0.02	<0.01	0.12	0.004	0.115	0.006	0.93	4.12	N.A.
646755	Drill Core	0.55	<0.01	0.173	27.17	0.02	0.18	<0.01	0.04	<0.01	0.27	0.002	0.148	0.007	1.37	4.05	N.A.
646756	Drill Core	1.21	<0.01	0.148	26.18	0.03	0.28	0.01	0.08	<0.01	0.47	0.003	0.178	0.008	1.62	3.64	N.A.
646757	Drill Core	0.78	<0.01	0.113	26.77	0.03	0.24	<0.01	0.05	<0.01	0.57	0.004	0.202	0.010	1.73	3.75	N.A.
646758	Drill Core	0.63	<0.01	0.150	25.37	0.03	0.28	<0.01	0.05	<0.01	0.64	0.002	0.254	0.012	1.52	4.18	N.A.
646759	Drill Core	0.46	<0.01	0.226	26.57	0.02	0.24	<0.01	0.05	<0.01	0.32	0.010	0.180	0.008	1.46	4.59	N.A.
646760A	Drill Core	0.89	<0.01	0.190	25.35	0.04	0.39	<0.01	0.09	<0.01	0.34	0.006	0.264	0.012	1.16	3.38	N.A.
646760B	Drill Core	0.90	<0.01	0.188	25.22	0.04	0.42	<0.01	0.10	<0.01	0.31	0.003	0.259	0.011	1.19	3.64	N.A.
646761	Drill Core	0.70	<0.01	0.130	26.41	0.03	0.32	<0.01	0.07	<0.01	0.25	0.007	0.176	0.010	1.20	4.67	N.A.
646762	Drill Core	0.91	0.01	0.132	25.56	0.03	0.27	<0.01	0.02	<0.01	0.12	0.005	0.145	0.008	1.06	4.79	3.02
646763	Drill Core	0.57	<0.01	0.166	27.06	0.03	0.26	<0.01	0.01	<0.01	0.06	0.001	0.094	0.005	1.21	4.85	N.A.
646764	Drill Core	0.86	<0.01	0.144	26.63	0.03	0.27	<0.01	0.03	<0.01	0.06	<0.001	0.089	0.005	1.01	4.19	N.A.
646765	Drill Core	0.76	<0.01	0.159	26.07	0.03	0.28	<0.01	0.02	<0.01	0.09	<0.001	0.115	0.006	1.09	4.33	N.A.
646766	Drill Core	0.83	<0.01	0.162	26.05	0.03	0.30	<0.01	0.04	<0.01	0.12	0.001	0.145	0.007	0.82	4.98	N.A.
646767	Drill Core	0.91	<0.01	0.117	26.09	0.04	0.29	<0.01	0.05	<0.01	0.10	<0.001	0.140	0.006	0.86	4.90	N.A.
646768	Drill Core	1.11	<0.01	0.124	26.36	0.04	0.29	<0.01	0.07	<0.01	0.13	0.001	0.142	0.006	0.81	4.88	N.A.
646769	Drill Core	1.48	<0.01	0.195	24.52	0.04	0.35	<0.01	0.07	<0.01	0.17	0.003	0.156	0.007	0.82	4.48	N.A.
646770	Drill Core	1.84	0.02	0.001	0.35	0.07	6.39	3.45	1.15	<0.01	0.02	<0.001	0.002	<0.001	0.07	0.11	N.A.
646771	Drill Core	0.50	<0.01	0.182	25.45	0.04	0.39	<0.01	0.11	<0.01	0.25	0.006	0.178	0.008	0.83	3.30	N.A.
646772	Drill Core	0.67	<0.01	0.187	25.14	0.06	0.61	<0.01	0.16	<0.01	0.41	0.010	0.195	0.011	0.86	3.04	N.A.
646773	Drill Core	3.36	<0.01	0.102	19.26	0.21	1.66	0.01	0.34	<0.01	0.56	0.014	0.143	0.010	0.55	1.12	N.A.
646774	Drill Core	5.75	<0.01	0.102	16.67	0.24	1.97	<0.01	0.25	<0.01	0.70	0.009	0.122	0.008	0.53	0.73	N.A.
646775	Rock Pulp	0.71	<0.01	0.172	24.51	0.02	0.31	<0.01	0.07	<0.01	1.15	0.001	0.222	0.014	1.44	4.00	N.A.
646776	Rock Pulp	4.32	0.01	0.952	13.24	0.18	3.91	0.33	0.11	<0.01	0.51	0.055	0.185	0.008	0.58	0.67	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 12, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000748.1

Method	WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646777	Drill Core	9.05	<2	<3	4	0.26	<0.001	0.003	<0.02	<0.01	<2	0.205	0.009	0.11	7.07	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646778	Drill Core	9.91	<2	<3	6	0.33	<0.001	0.004	<0.02	<0.01	<2	0.208	0.010	0.13	7.25	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646779	Drill Core	9.62	<2	6	9	0.32	<0.001	0.008	<0.02	<0.01	<2	0.218	0.011	0.13	7.52	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646780	Drill Core	9.53	<2	3	7	0.34	<0.001	0.006	<0.02	<0.01	<2	0.216	0.011	0.15	7.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646781	Drill Core	3.30	4	<3	3	0.47	<0.001	0.007	<0.02	0.03	<2	0.186	0.010	0.11	8.11	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 12, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000748.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%		
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
646777	Drill Core	2.20	<0.01	0.066	21.41	0.10	0.71	0.01	0.09	<0.01	0.27	0.003	0.172	0.008	0.50	1.94	N.A.
646778	Drill Core	1.94	<0.01	0.076	22.99	0.09	0.49	0.01	0.07	<0.01	0.32	0.004	0.157	0.008	0.70	2.75	N.A.
646779	Drill Core	0.49	<0.01	0.104	23.12	0.07	0.47	<0.01	0.08	<0.01	0.30	0.009	0.183	0.009	0.66	2.89	N.A.
646780	Drill Core	0.96	<0.01	0.114	23.47	0.07	0.45	<0.01	0.09	<0.01	0.32	0.006	0.176	0.009	0.75	3.04	N.A.
646781	Drill Core	0.90	<0.01	0.057	22.22	0.07	0.38	<0.01	0.05	<0.01	0.45	0.006	0.160	0.009	0.66	2.62	N.A.

QUALITY CONTROL REPORT

SMI08000748.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
Pulp Duplicates																					
646755	Drill Core	10.71	<2	51	52	0.31	<0.001	0.013	<0.02	<0.01	<2	0.281	0.014	0.12	7.54	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646755	QC					0.36															
646756	Drill Core	11.42	<2	25	16	0.63	<0.001	0.017	<0.02	<0.01	<2	0.273	0.015	0.13	8.34	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646756	QC					<0.001	0.017	<0.02	<0.01	<2	0.271	0.015	0.13	8.20	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	
646762	Drill Core	10.13	<2	25	20	0.12	<0.001	0.004	<0.02	<0.01	<2	0.270	0.013	0.12	7.63	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646762	QC																				
646767	Drill Core	10.82	<2	15	8	0.10	<0.001	<0.001	<0.02	<0.01	<2	0.278	0.011	0.09	5.74	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646767	QC																				
646770	Drill Core	1.02	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.002	<0.001	0.08	1.13	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
REP 646770	QC					<0.02															
646772	Drill Core	9.53	<2	6	24	0.45	<0.001	0.010	<0.02	<0.01	<2	0.252	0.015	0.12	7.18	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646772	QC					<0.001	0.010	<0.02	<0.01	<2	0.246	0.014	0.12	7.19	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	
646781	Drill Core	3.30	4	<3	3	0.47	<0.001	0.007	<0.02	0.03	<2	0.186	0.010	0.11	8.11	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646781	QC		4	<3	4																
Core Reject Duplicates																					
646761	Drill Core	10.13	<2	55	49	0.19	<0.001	0.009	<0.02	<0.01	<2	0.266	0.016	0.13	8.39	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
DUP 646761	QC		<2	61	48	0.17	<0.001	0.007	<0.02	<0.01	<2	0.263	0.016	0.13	8.18	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
Reference Materials																					
STD CDN-PGMS-14	Standard		234	109	420																
STD CDN-PGMS-14	Standard		274	126	432																
STD CDN-PGMS-14	Standard		234	115	419																
STD CSC	Standard					4.15															
STD CSC	Standard					4.33															
STD FA10R	Standard		462	458	464																
STD FA10R	Standard		525	505	487																
STD FA10R	Standard		464	472	456																
STD OREAS76A	Standard					17.49															
STD OREAS76A	Standard					17.05															

QUALITY CONTROL REPORT

SMI08000748.1

Method		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
Unit		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
Pulp Duplicates																	
646755	Drill Core	0.55	<0.01	0.173	27.17	0.02	0.18	<0.01	0.04	<0.01	0.27	0.002	0.148	0.007	1.37	4.05	N.A.
REP 646755	QC																
646756	Drill Core	1.21	<0.01	0.148	26.18	0.03	0.28	0.01	0.08	<0.01	0.47	0.003	0.178	0.008	1.62	3.64	N.A.
REP 646756	QC	1.22	<0.01	0.158	26.25	0.03	0.28	0.01	0.07	<0.01	0.46						
646762	Drill Core	0.91	0.01	0.132	25.56	0.03	0.27	<0.01	0.02	<0.01	0.12	0.005	0.145	0.008	1.06	4.79	3.02
REP 646762	QC											0.005	0.144	0.008	1.05	4.73	
646767	Drill Core	0.91	<0.01	0.117	26.09	0.04	0.29	<0.01	0.05	<0.01	0.10	<0.001	0.140	0.006	0.86	4.90	N.A.
REP 646767	QC											<0.001	0.135	0.005	0.82	4.72	
646770	Drill Core	1.84	0.02	0.001	0.35	0.07	6.39	3.45	1.15	<0.01	0.02	<0.001	0.002	<0.001	0.07	0.11	N.A.
REP 646770	QC																
646772	Drill Core	0.67	<0.01	0.187	25.14	0.06	0.61	<0.01	0.16	<0.01	0.41	0.010	0.195	0.011	0.86	3.04	N.A.
REP 646772	QC	0.64	<0.01	0.180	23.37	0.06	0.58	<0.01	0.14	<0.01	0.39						
646781	Drill Core	0.90	<0.01	0.057	22.22	0.07	0.38	<0.01	0.05	<0.01	0.45	0.006	0.160	0.009	0.66	2.62	N.A.
REP 646781	QC																
Core Reject Duplicates																	
646761	Drill Core	0.70	<0.01	0.130	26.41	0.03	0.32	<0.01	0.07	<0.01	0.25	0.007	0.176	0.010	1.20	4.67	N.A.
DUP 646761	QC	0.72	<0.01	0.120	26.32	0.03	0.31	<0.01	0.07	<0.01	0.18	0.005	0.169	0.009	1.23	4.62	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																
STD OREAS76A	Standard																

QUALITY CONTROL REPORT

SMI08000748.1

	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
STD SF-3A_NI	Standard																				
STD SF-3A_NI	Standard																				
STD SF-3T	Standard					0.030	0.775	0.90	1.08	51	0.347	0.017	0.42	8.14	<0.02	0.04	0.004	<0.01	<0.01	0.01	
STD SF-3T	Standard					0.031	0.794	0.92	1.10	52	0.353	0.018	0.43	8.28	<0.02	0.04	0.005	<0.01	<0.01	0.01	
STD SF-3T	Standard					0.031	0.772	0.92	1.07	54	0.350	0.018	0.42	8.13	<0.02	0.04	0.004	<0.01	<0.01	0.01	
STD SF-3T	Standard					0.031	0.757	0.89	1.06	53	0.344	0.017	0.42	8.01	<0.02	0.04	0.004	<0.01	<0.01	0.01	
STD SF-3T Expected						0.032	0.7723	0.961	1.0672	52	0.35	0.0181	0.432	8.33	0.004	0.044	0.00475	0.00111	0.00048	0.0143	
STD CSC Expected						4.19															
STD OREAS76A Expected						18															
STD SF-3A_NI Expected																					
STD FA10R Expected		485	472	476																	
STD CDN-PGMS-14		259	119	451																	
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
BLK	Blank				<0.02																
BLK	Blank				<0.02																
BLK	Blank																				
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
BLK	Blank																				
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
Prep Wash																					
G1	Prep Blank	<0.01	26	13	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.13	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank	<0.01	23	13	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.08	2.17	<0.02	0.07	<0.001	<0.01	<0.01	<0.01

QUALITY CONTROL REPORT

SMI08000748.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
STD SF-3A_NI	Standard											0.066	0.336	0.017	3.64	3.39	
STD SF-3A_NI	Standard											0.091	0.343	0.018	4.03	3.42	
STD SF-3T	Standard	4.01	0.05	0.016	4.57	0.19	5.33	2.05	2.46	<0.01	3.95						
STD SF-3T	Standard	4.07	0.05	0.017	4.67	0.20	5.42	2.07	2.50	<0.01	4.14						
STD SF-3T	Standard	4.01	0.06	0.019	4.57	0.20	5.31	2.03	2.41	<0.01	4.13						
STD SF-3T	Standard	3.98	0.05	0.019	4.50	0.19	5.27	2.02	2.37	<0.01	3.96						
STD SF-3T Expected		4.1	0.06	0.02074	4.67	0.19	5.43	2.06	2.47	0.00043	3.5						
STD CSC Expected																	
STD OREAS76A Expected																	
STD SF-3A_NI Expected												0.3205					
STD FA10R Expected																	
STD CDN-PGMS-14																	
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank																
BLK	Blank																
Prep Wash																	
G1	Prep Blank	2.31	0.07	0.002	0.70	0.22	8.12	2.59	2.99	<0.01	<0.01	<0.001	<0.001	<0.001	0.09	0.05	N.A.
G1	Prep Blank	2.37	0.07	0.001	0.69	0.23	8.38	2.65	3.08	<0.01	<0.01	0.008	<0.001	<0.001	0.13	0.07	N.A.

Hole 08-258



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By:
 Receiving Lab: Canada-Smithers
 Received: August 07, 2008
 Report Date: September 02, 2008
 Page: 1 of 2

CERTIFICATE OF ANALYSIS

SMI08000700.1

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-258A
 P.O. Number
 Number of Samples: 17

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	16	Crush split and pulverize drill core to 200 mesh		
3B	16	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	17	Analysis by Leco	0.1	Completed
7TD	17	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	17	Leached with H2O2 + NH4 citrate	1	Completed
Specific Gravity	2	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 02, 2008

Page: 2 of 2 Part 1

CERTIFICATE OF ANALYSIS

SMI08000700.1

Method	WGHT	3B	3B	3B2A	LECO	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646782	Drill Core	7.33	<2	<3	5	0.07	<0.001	0.008	<0.02	<0.01	<2	0.231	0.013	0.13	8.19	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646783	Drill Core	11.89	7	8	15	0.10	<0.001	0.008	<0.02	<0.01	<2	0.242	0.013	0.14	8.69	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646784	Drill Core	11.20	2	9	19	0.11	<0.001	0.006	<0.02	<0.01	<2	0.210	0.012	0.14	8.87	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646785	Drill Core	11.62	3	11	18	0.15	<0.001	0.011	<0.02	<0.01	<2	0.213	0.013	0.14	8.98	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646786	Drill Core	12.08	<2	9	14	0.39	<0.001	0.015	<0.02	<0.01	<2	0.205	0.013	0.14	9.39	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646787	Drill Core	11.27	<2	3	9	0.47	<0.001	0.017	<0.02	<0.01	<2	0.190	0.012	0.14	9.30	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646788	Drill Core	11.08	<2	8	10	0.25	<0.001	0.009	<0.02	<0.01	<2	0.221	0.012	0.13	8.25	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646789	Drill Core	11.34	<2	<3	7	0.40	<0.001	0.016	<0.02	<0.01	<2	0.223	0.013	0.13	8.24	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646790A	Drill Core	11.47	<2	16	11	0.79	<0.001	0.022	<0.02	<0.01	<2	0.139	0.011	0.12	8.71	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646790B	Drill Core		<2	14	13	0.81	<0.001	0.022	<0.02	<0.01	<2	0.139	0.011	0.12	8.58	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646791	Drill Core	10.59	<2	12	17	1.13	<0.001	0.024	<0.02	<0.01	<2	0.187	0.011	0.14	10.74	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646792	Drill Core	8.33	<2	17	19	1.18	<0.001	0.023	<0.02	<0.01	<2	0.175	0.012	0.10	9.88	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646793	Drill Core	12.21	<2	7	11	0.90	<0.001	0.019	<0.02	<0.01	<2	0.222	0.013	0.15	10.18	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646794	Drill Core	11.01	<2	12	17	1.11	<0.001	0.030	<0.02	<0.01	<2	0.193	0.013	0.15	9.97	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646795	Drill Core	11.32	<2	19	21	2.09	<0.001	0.075	<0.02	<0.01	<2	0.221	0.021	0.13	11.73	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646796	Drill Core	11.82	<2	25	35	1.48	<0.001	0.051	<0.02	<0.01	<2	0.313	0.021	0.13	11.16	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646796 STD	Rock Pulp	0.02	I.S.	I.S.	I.S.	4.34	<0.001	0.049	<0.02	<0.01	<2	0.414	0.028	0.12	13.61	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 02, 2008

Page: 2 of 2 Part 2

CERTIFICATE OF ANALYSIS

SMI08000700.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
646782	Drill Core	0.57	<0.01	0.221	25.93	0.01	0.11	<0.01	0.01	<0.01	0.08	0.007	0.070	0.004	0.58	2.00	3.17
646783	Drill Core	0.61	<0.01	0.180	25.08	0.01	0.09	0.01	0.01	<0.01	0.11	0.008	0.086	0.004	0.65	1.99	N.A.
646784	Drill Core	1.04	<0.01	0.228	25.07	0.02	0.13	0.01	<0.01	<0.01	0.13	0.005	0.070	0.004	0.64	1.89	N.A.
646785	Drill Core	1.08	<0.01	0.181	25.54	0.02	0.13	0.01	<0.01	<0.01	0.12	0.012	0.074	0.004	0.72	1.97	N.A.
646786	Drill Core	1.87	<0.01	0.145	23.46	0.02	0.11	0.02	<0.01	<0.01	0.42	0.015	0.127	0.006	0.63	1.38	N.A.
646787	Drill Core	2.52	<0.01	0.146	23.33	0.02	0.10	0.02	<0.01	<0.01	0.46	0.017	0.124	0.006	0.69	1.48	N.A.
646788	Drill Core	1.47	<0.01	0.127	24.48	0.02	0.08	0.02	<0.01	<0.01	0.26	0.009	0.101	0.005	0.57	1.53	N.A.
646789	Drill Core	1.45	<0.01	0.175	25.21	0.01	0.08	0.01	<0.01	<0.01	0.39	0.017	0.114	0.006	0.55	1.41	N.A.
646790A	Drill Core	4.59	<0.01	0.134	20.51	0.04	0.19	0.04	<0.01	<0.01	0.74	0.022	0.115	0.007	0.52	1.03	N.A.
646790B	Drill Core	4.60	<0.01	0.138	20.51	0.04	0.18	0.04	<0.01	<0.01	0.73	0.020	0.108	0.007	0.49	0.95	N.A.
646791	Drill Core	2.77	<0.01	0.137	21.96	0.03	0.14	0.02	<0.01	<0.01	0.99	0.023	0.154	0.008	0.61	1.23	N.A.
646792	Drill Core	2.27	<0.01	0.143	20.02	0.02	0.30	0.01	<0.01	<0.01	1.03	0.023	0.190	0.011	0.56	0.91	3.18
646793	Drill Core	2.65	<0.01	0.144	22.91	0.03	0.13	0.02	<0.01	<0.01	0.81	0.016	0.168	0.008	0.51	0.92	N.A.
646794	Drill Core	3.59	<0.01	0.163	21.61	0.03	0.16	0.03	<0.01	<0.01	0.98	0.028	0.157	0.008	0.57	0.99	N.A.
646795	Drill Core	3.69	<0.01	0.140	20.77	0.03	0.15	0.03	<0.01	<0.01	1.66	0.075	0.222	0.017	0.87	1.30	N.A.
646796	Drill Core	0.50	<0.01	0.222	24.43	0.01	0.09	<0.01	<0.01	<0.01	1.13	0.050	0.279	0.014	0.91	1.54	N.A.
646796 STD	Rock Pulp	1.18	<0.01	0.184	21.50	0.02	0.29	0.03	0.10	<0.01	3.07	0.049	0.427	0.025	1.13	1.64	N.A.

QUALITY CONTROL REPORT

SMI08000700.1

Method	WGHT	3B	3B	3B2A	LECO	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
Pulp Duplicates																					
646788	Drill Core	11.08	<2	8	10	0.25	<0.001	0.009	<0.02	<0.01	<2	0.221	0.012	0.13	8.25	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646788	QC		<2	7	9																
646789	Drill Core	11.34	<2	<3	7	0.40	<0.001	0.016	<0.02	<0.01	<2	0.223	0.013	0.13	8.24	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646789	QC																				
646796	Drill Core	11.82	<2	25	35	1.48	<0.001	0.051	<0.02	<0.01	<2	0.313	0.021	0.13	11.16	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646796	QC						<0.001	0.051	<0.02	<0.01	<2	0.316	0.021	0.13	11.19	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
Core Reject Duplicates																					
646786	Drill Core	12.08	<2	9	14	0.39	<0.001	0.015	<0.02	<0.01	<2	0.205	0.013	0.14	9.39	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
DUP 646786	QC		36	6	8	0.43	<0.001	0.014	<0.02	<0.01	<2	0.204	0.013	0.14	9.34	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
Reference Materials																					
STD CDN-PGMS-14	Standard		229	101	408																
STD CSC	Standard					4.31															
STD FA10R	Standard		459	443	452																
STD OREAS76A	Standard					17.92															
STD R3NI	Standard																				
STD R3NI	Standard																				
STD R3T	Standard					0.076	0.800	1.98	4.08	194	0.535	0.061	0.09	32.89	<0.02	<0.01	0.024	0.03	<0.01	0.02	
STD R3T	Standard					0.077	0.805	2.02	4.16	196	0.541	0.062	0.09	33.09	<0.02	<0.01	0.024	0.03	<0.01	0.02	
STD R3T Expected						0.077	0.805	1.98	4.1	190	0.525	0.061	0.09	34.17	0.04	0.01	0.024	0.04			
STD CSC Expected						4.19															
STD OREAS76A Expected						18															
STD R3NI Expected																					
STD FA10R Expected			485	472	476																
STD CDN-PGMS-14			259	119	451																
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank					<0.02															
BLK	Blank																				
BLK	Blank																				

QUALITY CONTROL REPORT

SMI08000700.1

Method		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
Unit		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
Pulp Duplicates																	
646788	Drill Core	1.47	<0.01	0.127	24.48	0.02	0.08	0.02	<0.01	<0.01	0.26	0.009	0.101	0.005	0.57	1.53	N.A.
REP 646788	QC																
646789	Drill Core	1.45	<0.01	0.175	25.21	0.01	0.08	0.01	<0.01	<0.01	0.39	0.017	0.114	0.006	0.55	1.41	N.A.
REP 646789	QC											0.016	0.109	0.006	0.52	1.39	
646796	Drill Core	0.50	<0.01	0.222	24.43	0.01	0.09	<0.01	<0.01	<0.01	1.13	0.050	0.279	0.014	0.91	1.54	N.A.
REP 646796	QC	0.50	<0.01	0.224	24.30	0.01	0.09	<0.01	<0.01	<0.01	1.15						
Core Reject Duplicates																	
646786	Drill Core	1.87	<0.01	0.145	23.46	0.02	0.11	0.02	<0.01	<0.01	0.42	0.015	0.127	0.006	0.63	1.38	N.A.
DUP 646786	QC	1.91	<0.01	0.150	23.42	0.02	0.11	0.02	<0.01	<0.01	0.43	0.014	0.126	0.006	0.65	1.48	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																
STD R3NI	Standard											0.714	0.393	0.051	4.46	0.15	
STD R3NI	Standard											0.743	0.394	0.052	3.07	0.13	
STD R3T	Standard	2.19	0.05	0.020	1.66	0.17	2.45	0.31	0.60	<0.01	16.50						
STD R3T	Standard	2.23	0.05	0.020	1.67	0.18	2.47	0.32	0.60	<0.01	16.78						
STD R3T Expected		2.23	0.05	0.02	1.64		2.44	0.31	0.59								
STD CSC Expected																	
STD OREAS76A Expected																	
STD R3NI Expected													0.42				
STD FA10R Expected																	
STD CDN-PGMS-14																	
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	

QUALITY CONTROL REPORT

SMI08000700.1

		WGHT	3B	3B	3B2A	LECO	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2	0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.33	<0.02	0.06	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank	<0.01	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.29	<0.02	0.07	<0.001	<0.01	<0.01	<0.01

QUALITY CONTROL REPORT

SMI08000700.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NIS	8NIS	8NIS	8NIS	8NIS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
BLK	Blank																
BLK	Blank																
Prep Wash																	
G1	Prep Blank	2.22	0.07	<0.001	0.62	0.22	6.60	2.54	3.00	<0.01	<0.01	<0.001	<0.001	<0.001	0.17	0.06	N.A.
G1	Prep Blank	2.28	0.07	<0.001	0.59	0.22	7.16	2.66	2.97	<0.01	0.03	<0.001	<0.001	<0.001	0.13	0.04	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By:
 Receiving Lab: Canada-Smithers
 Received: August 14, 2008
 Report Date: September 12, 2008
 Page: 1 of 2

CERTIFICATE OF ANALYSIS

SMI08000749.1

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-258B
 P.O. Number
 Number of Samples: 15

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	13	Crush split and pulverize drill core to 200 mesh		
3B	15	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	15	Analysis by Leco	0.1	Completed
7TD	15	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	15	Leached with H2O2 + NH4 citrate	1	Completed
Specific Gravity	1	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 12, 2008

Page: 2 of 2 Part 1

CERTIFICATE OF ANALYSIS

SMI08000749.1

Method	WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646797	Drill Core	10.87	3	22	25	0.41	<0.001	0.028	<0.02	<0.01	<2	0.276	0.014	0.12	7.72	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646798	Drill Core	11.05	<2	7	16	0.60	<0.001	0.021	<0.02	<0.01	<2	0.192	0.016	0.13	8.56	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646799	Drill Core	12.02	<2	7	16	1.17	<0.001	0.033	<0.02	<0.01	<2	0.220	0.019	0.14	9.88	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646800	Rock Pulp	0.02	I.S.	I.S.	I.S.	0.48	<0.001	0.055	<0.02	0.02	<2	0.240	0.011	0.11	8.60	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646801	Rock Pulp	0.02	I.S.	I.S.	I.S.	1.41	<0.001	0.031	<0.02	<0.01	<2	0.259	0.017	0.12	8.72	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646802	Drill Core	12.22	<2	5	11	0.83	<0.001	0.017	<0.02	<0.01	<2	0.195	0.015	0.14	9.20	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646803	Drill Core	12.49	<2	7	11	1.44	<0.001	0.032	<0.02	<0.01	<2	0.197	0.014	0.14	9.82	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646804	Drill Core	12.27	<2	19	22	0.95	<0.001	0.017	<0.02	0.01	<2	0.286	0.015	0.16	9.69	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646805	Drill Core	11.24	<2	11	10	0.83	<0.001	0.016	<0.02	<0.01	<2	0.133	0.011	0.13	8.66	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646806	Drill Core	10.98	<2	<3	3	1.07	<0.001	0.021	<0.02	<0.01	<2	0.117	0.012	0.13	7.79	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646807	Drill Core	12.10	<2	22	16	1.35	<0.001	0.026	<0.02	<0.01	<2	0.130	0.012	0.13	7.90	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646808	Drill Core	11.87	<2	7	9	1.67	<0.001	0.033	<0.02	<0.01	<2	0.065	0.012	0.11	7.02	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646809	Drill Core	5.41	<2	<3	<2	1.71	<0.001	0.026	<0.02	<0.01	<2	0.027	0.011	0.12	7.62	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646810	Drill Core	5.19	<2	4	<2	0.10	<0.001	0.004	<0.02	<0.01	<2	0.001	0.002	0.13	4.59	<0.02	0.11	<0.001	<0.01	<0.01	0.02
646811	Drill Core	9.67	<2	13	16	0.66	<0.001	0.016	<0.02	<0.01	<2	0.119	0.008	0.12	6.23	<0.02	0.04	<0.001	<0.01	<0.01	0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 12, 2008

Page: 2 of 2 Part 2

CERTIFICATE OF ANALYSIS

SMI08000749.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
646797	Drill Core	0.63	<0.01	0.196	25.29	0.01	0.10	0.01	<0.01	<0.01	0.38	0.015	0.172	0.008	1.20	4.40	N.A.
646798	Drill Core	1.82	<0.01	0.261	24.05	0.02	0.18	0.02	<0.01	<0.01	0.55	0.001	0.120	0.010	1.43	3.56	N.A.
646799	Drill Core	1.13	<0.01	0.186	25.01	0.02	0.09	0.01	<0.01	<0.01	0.96	0.003	0.160	0.013	1.65	3.10	N.A.
646800	Rock Pulp	4.34	<0.01	0.965	13.53	0.19	3.90	0.32	0.11	<0.01	0.50	0.059	0.188	0.008	0.61	0.70	N.A.
646801	Rock Pulp	0.71	<0.01	0.173	24.04	0.02	0.32	<0.01	0.07	<0.01	1.16	0.001	0.221	0.014	1.45	4.00	N.A.
646802	Drill Core	1.49	<0.01	0.208	24.54	0.02	0.11	0.01	<0.01	<0.01	0.70	0.004	0.140	0.010	1.86	3.87	3.25
646803	Drill Core	3.92	<0.01	0.207	21.27	0.04	0.18	0.03	<0.01	<0.01	1.13	0.010	0.150	0.010	1.89	2.53	N.A.
646804	Drill Core	2.01	<0.01	0.175	23.85	0.03	0.13	0.02	<0.01	<0.01	0.82	0.011	0.205	0.010	1.75	3.43	N.A.
646805	Drill Core	5.03	<0.01	0.144	19.68	0.08	0.38	0.04	<0.01	<0.01	0.78	0.016	0.108	0.009	1.07	2.62	N.A.
646806	Drill Core	6.99	<0.01	0.159	17.56	0.08	0.36	0.05	0.01	<0.01	0.92	0.012	0.089	0.009	1.57	2.31	N.A.
646807	Drill Core	8.27	<0.01	0.156	15.97	0.10	0.40	0.07	<0.01	<0.01	1.09	0.013	0.112	0.010	1.70	1.82	N.A.
646808	Drill Core	11.19	<0.01	0.189	12.70	0.13	0.51	0.08	<0.01	<0.01	1.43	0.034	0.061	0.011	1.03	0.87	N.A.
646809	Drill Core	10.72	<0.01	0.127	12.95	0.13	0.69	0.09	0.05	<0.01	1.47	0.027	0.026	0.010	1.15	0.91	N.A.
646810	Drill Core	6.41	0.11	0.003	1.79	0.28	7.66	3.95	1.45	<0.01	0.12	0.006	<0.001	<0.001	0.18	0.05	N.A.
646811	Drill Core	5.47	0.04	0.100	13.23	0.16	3.76	0.82	1.00	<0.01	0.59	0.018	0.099	0.005	0.51	0.45	N.A.

QUALITY CONTROL REPORT

SMI08000749.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
Pulp Duplicates																					
646797	Drill Core	10.87	3	22	25	0.41	<0.001	0.028	<0.02	<0.01	<2	0.276	0.014	0.12	7.72	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646797	QC																				
Core Reject Duplicates																					
646810	Drill Core	5.19	<2	4	<2	0.10	<0.001	0.004	<0.02	<0.01	<2	0.001	0.002	0.13	4.59	<0.02	0.11	<0.001	<0.01	<0.01	0.02
DUP 646810	QC		<2	4	<2	0.10	<0.001	0.005	<0.02	<0.01	<2	0.001	0.002	0.13	4.67	<0.02	0.11	<0.001	<0.01	<0.01	0.02
Reference Materials																					
STD CDN-PGMS-14	Standard		235	103	419																
STD CDN-PGMS-14	Standard		234	109	420																
STD CSC	Standard					4.15															
STD CSC	Standard					4.26															
STD FA10R	Standard		475	460	477																
STD FA10R	Standard		462	458	464																
STD OREAS76A	Standard					17.49															
STD OREAS76A	Standard					18.07															
STD SF-3A_NI	Standard																				
STD SF-3T	Standard					0.031	0.772	0.92	1.07	54	0.350	0.018	0.42	8.13	<0.02	0.04	0.004	<0.01	<0.01	0.01	
STD SF-3T	Standard					0.031	0.757	0.89	1.06	53	0.344	0.017	0.42	8.01	<0.02	0.04	0.004	<0.01	<0.01	0.01	
STD SF-3T	Standard					0.031	0.755	0.94	1.04	52	0.344	0.018	0.43	8.13	<0.02	0.04	0.005	<0.01	<0.01	0.01	
STD SF-3T	Standard					0.031	0.766	0.94	1.05	54	0.346	0.018	0.44	8.22	<0.02	0.04	0.005	<0.01	<0.01	0.01	
STD SF-3T Expected						0.032	0.7723	0.961	1.0672	52	0.35	0.0181	0.432	8.33	0.004	0.044	0.00475	0.00111	0.00048	0.0143	
STD FA10R Expected			485	472	476																
STD CDN-PGMS-14			259	119	451																
STD CSC Expected						4.19															
STD OREAS76A Expected						18															
STD SF-3A_NI Expected																					
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	
BLK	Blank		<2	<3	<2																

QUALITY CONTROL REPORT

SMI08000749.1

Method		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
Unit		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
Pulp Duplicates																	
646797	Drill Core	0.63	<0.01	0.196	25.29	0.01	0.10	0.01	<0.01	<0.01	0.38	0.015	0.172	0.008	1.20	4.40	N.A.
REP 646797	QC											0.017	0.172	0.008	1.20	4.38	
Core Reject Duplicates																	
646810	Drill Core	6.41	0.11	0.003	1.79	0.28	7.66	3.95	1.45	<0.01	0.12	0.006	<0.001	<0.001	0.18	0.05	N.A.
DUP 646810	QC	6.48	0.11	0.003	1.81	0.29	8.09	3.87	1.47	<0.01	0.12	0.006	<0.001	<0.001	0.18	0.05	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																
STD OREAS76A	Standard																
STD SF-3A_NI	Standard											0.066	0.336	0.017	3.64	3.39	
STD SF-3T	Standard	4.01	0.06	0.019	4.57	0.20	5.31	2.03	2.41	<0.01	4.13						
STD SF-3T	Standard	3.98	0.05	0.019	4.50	0.19	5.27	2.02	2.37	<0.01	3.96						
STD SF-3T	Standard	4.07	0.06	0.017	4.58	0.20	5.34	2.06	2.50	<0.01	4.02						
STD SF-3T	Standard	4.11	0.06	0.018	4.62	0.20	5.39	2.08	2.52	<0.01	4.05						
STD SF-3T Expected		4.1	0.06	0.02074	4.67	0.19	5.43	2.06	2.47	0.00043	3.5						
STD FA10R Expected																	
STD CDN-PGMS-14																	
STD CSC Expected																	
STD OREAS76A Expected																	
STD SF-3A_NI Expected												0.3205					
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																

QUALITY CONTROL REPORT

SMI08000749.1

		WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank					<0.02															
BLK	Blank					<0.02															
BLK	Blank																				
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.08	2.29	<0.02	0.06	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank	<0.01	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.08	2.25	<0.02	0.06	<0.001	<0.01	<0.01	<0.01

QUALITY CONTROL REPORT

SMI08000749.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
Prep Wash																	
G1	Prep Blank	2.50	0.07	<0.001	0.69	0.22	7.01	2.56	2.94	<0.01	0.03	<0.001	<0.001	<0.001	0.13	0.15	N.A.
G1	Prep Blank	2.30	0.07	0.001	0.60	0.23	6.98	2.57	2.98	<0.01	0.02	<0.001	<0.001	<0.001	0.17	0.06	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Email Distribution List
 Receiving Lab: Canada-Smithers
 Received: August 18, 2008
 Report Date: September 17, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000760.1

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-258C
 P.O. Number
 Number of Samples: 36

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC: Email Distribution List

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	34	Crush split and pulverize drill core to 200 mesh		
3B	36	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	36	Analysis by Leco	0.1	Completed
7TD	36	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	36	Leached with H2O2 + NH4 citrate	1	Completed
Specific Gravity	3	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 17, 2008

Page: 2 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000760.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646812	Drill Core	11.52	4	36	37	0.56	<0.001	0.020	<0.02	<0.01	<2	0.301	0.014	0.14	8.08	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646813	Drill Core	11.33	5	15	18	2.16	<0.001	0.069	<0.02	<0.01	<2	0.243	0.022	0.14	11.23	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646814	Drill Core	11.60	<2	53	37	2.24	<0.001	0.054	<0.02	<0.01	<2	0.293	0.018	0.15	10.78	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646815	Drill Core	10.93	22	139	140	2.99	<0.001	0.142	<0.02	<0.01	<2	0.716	0.025	0.13	11.27	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646816	Drill Core	11.33	9	224	231	4.58	<0.001	0.179	<0.02	<0.01	<2	1.080	0.034	0.12	13.57	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646817	Drill Core	11.71	22	124	124	3.05	<0.001	0.087	<0.02	<0.01	<2	0.883	0.028	0.14	11.62	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646818	Drill Core	10.91	24	136	160	1.27	<0.001	0.067	<0.02	<0.01	2	0.657	0.018	0.15	9.82	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646819	Drill Core	4.28	6	51	66	1.23	<0.001	0.046	<0.02	<0.01	<2	0.343	0.016	0.15	10.27	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646820A	Drill Core	7.01	5	106	96	2.99	<0.001	0.067	<0.02	<0.01	<2	0.390	0.021	0.12	10.54	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
646820B	Drill Core		6	90	83	2.79	<0.001	0.066	<0.02	<0.01	<2	0.351	0.018	0.12	10.06	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
646821	Drill Core	11.76	3	31	34	0.63	<0.001	0.014	<0.02	<0.01	<2	0.249	0.012	0.14	9.41	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646822	Drill Core	11.87	5	18	15	1.33	<0.001	0.055	<0.02	<0.01	<2	0.270	0.020	0.14	10.45	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646823	Drill Core	6.75	3	28	26	3.01	0.001	0.091	<0.02	<0.01	<2	0.332	0.030	0.13	12.48	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646824	Drill Core	5.19	<2	7	8	0.33	<0.001	0.004	<0.02	<0.01	<2	0.197	0.010	0.15	8.30	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646825	Rock Pulp	0.07	I.S.	I.S.	I.S.	1.37	<0.001	0.032	<0.02	<0.01	<2	0.251	0.017	0.12	8.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646826	Rock Pulp	0.06	I.S.	I.S.	I.S.	0.46	<0.001	0.057	<0.02	0.02	2	0.232	0.012	0.11	9.11	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646827	Drill Core	11.32	<2	<3	6	0.84	<0.001	0.012	<0.02	<0.01	<2	0.171	0.013	0.14	8.28	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646828	Drill Core	10.59	<2	6	7	0.92	<0.001	0.011	<0.02	<0.01	<2	0.241	0.015	0.12	8.33	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646829	Drill Core	11.32	<2	10	10	0.56	<0.001	0.008	<0.02	<0.01	<2	0.267	0.014	0.13	8.07	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646830	Drill Core	1.17	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.002	<0.001	0.07	1.11	<0.02	0.08	<0.001	<0.01	<0.01	<0.01
646831	Drill Core	10.38	<2	6	3	0.25	<0.001	0.003	<0.02	<0.01	<2	0.233	0.011	0.13	7.19	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646832	Drill Core	9.64	<2	6	5	0.50	<0.001	0.007	<0.02	<0.01	<2	0.226	0.011	0.13	6.90	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646833	Drill Core	9.62	<2	11	19	0.96	<0.001	0.015	<0.02	<0.01	<2	0.208	0.015	0.14	8.80	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646834	Drill Core	11.30	<2	4	9	1.41	<0.001	0.024	<0.02	<0.01	<2	0.194	0.019	0.14	10.28	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646835	Drill Core	11.10	<2	7	<2	0.46	<0.001	0.006	<0.02	<0.01	<2	0.182	0.010	0.15	8.40	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646836	Drill Core	11.31	<2	8	<2	0.49	<0.001	0.006	<0.02	<0.01	<2	0.174	0.010	0.13	7.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646837	Drill Core	11.89	<2	6	14	2.25	<0.001	0.035	<0.02	<0.01	<2	0.145	0.021	0.15	11.79	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646838	Drill Core	10.53	3	15	8	1.76	<0.001	0.023	<0.02	<0.01	<2	0.137	0.013	0.16	12.08	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646839	Drill Core	10.65	5	12	9	0.73	<0.001	0.011	<0.02	0.01	<2	0.195	0.011	0.15	9.28	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646840	Drill Core	10.29	4	5	10	1.57	0.002	0.021	<0.02	0.02	<2	0.126	0.012	0.16	10.69	<0.02	<0.01	<0.001	<0.01	<0.01	0.04



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 17, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000760.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
646812	Drill Core	1.40	<0.01	0.116	24.73	0.02	0.21	0.02	0.02	<0.01	0.50	0.018	0.206	0.009	1.00	2.64	3.15
646813	Drill Core	1.52	<0.01	0.151	23.17	0.03	0.23	0.02	<0.01	<0.01	1.61	0.070	0.220	0.019	1.73	3.11	N.A.
646814	Drill Core	1.87	<0.01	0.161	24.06	0.02	0.13	0.02	<0.01	<0.01	1.66	0.052	0.266	0.015	1.60	2.90	N.A.
646815	Drill Core	1.28	<0.01	0.132	23.04	0.03	0.19	0.01	<0.01	<0.01	2.25	0.136	0.698	0.023	2.29	3.16	N.A.
646816	Drill Core	1.75	<0.01	0.119	21.67	0.02	0.14	0.01	<0.01	<0.01	3.28	0.181	1.077	0.033	3.10	2.33	N.A.
646817	Drill Core	1.74	<0.01	0.119	23.07	0.02	0.13	0.02	<0.01	<0.01	2.37	0.090	0.825	0.024	2.52	2.84	N.A.
646818	Drill Core	1.48	<0.01	0.168	23.91	0.02	0.15	0.01	<0.01	<0.01	1.07	0.068	0.566	0.014	1.68	2.87	N.A.
646819	Drill Core	2.89	<0.01	0.187	22.31	0.03	0.19	0.03	<0.01	<0.01	1.00	0.046	0.278	0.011	1.29	2.41	N.A.
646820A	Drill Core	8.12	<0.01	0.197	15.73	0.05	0.33	0.07	0.02	<0.01	2.13	0.068	0.376	0.019	1.86	1.40	N.A.
646820B	Drill Core	7.98	<0.01	0.177	16.28	0.05	0.31	0.06	0.01	<0.01	1.81	0.070	0.341	0.017	1.69	1.33	N.A.
646821	Drill Core	1.69	<0.01	0.100	25.09	0.01	0.11	0.02	<0.01	<0.01	0.55	0.013	0.172	0.007	1.14	2.80	N.A.
646822	Drill Core	0.46	<0.01	0.133	26.58	<0.01	0.07	<0.01	<0.01	<0.01	1.06	0.055	0.218	0.014	1.56	3.32	2.76
646823	Drill Core	1.15	<0.01	0.151	23.48	0.01	0.09	<0.01	<0.01	<0.01	2.25	0.091	0.303	0.026	1.80	2.69	N.A.
646824	Drill Core	3.28	<0.01	0.098	23.96	0.02	0.15	0.03	<0.01	<0.01	0.30	0.004	0.114	0.005	0.93	2.46	N.A.
646825	Rock Pulp	0.73	<0.01	0.141	25.42	0.02	0.32	<0.01	0.07	<0.01	1.08	0.032	0.222	0.013	1.27	3.75	N.A.
646826	Rock Pulp	4.45	<0.01	1.071	14.04	0.19	4.17	0.34	0.12	<0.01	0.46	0.058	0.184	0.007	0.53	0.51	N.A.
646827	Drill Core	3.65	<0.01	0.116	22.92	0.02	0.15	0.03	<0.01	<0.01	0.68	0.010	0.125	0.008	1.04	2.49	N.A.
646828	Drill Core	3.61	<0.01	0.131	22.72	0.02	0.16	0.03	<0.01	<0.01	0.74	0.009	0.193	0.010	1.11	2.54	N.A.
646829	Drill Core	1.96	<0.01	0.250	25.82	0.02	0.14	0.02	<0.01	<0.01	0.48	0.006	0.159	0.007	1.12	3.11	N.A.
646830	Drill Core	1.98	0.02	<0.001	0.32	0.07	7.98	3.58	1.16	<0.01	<0.01	<0.001	0.001	<0.001	0.08	0.06	N.A.
646831	Drill Core	1.90	<0.01	0.064	25.50	0.01	0.10	0.02	<0.01	<0.01	0.25	<0.001	0.116	0.005	1.06	3.58	N.A.
646832	Drill Core	2.23	<0.01	0.104	23.61	0.02	0.16	0.02	0.02	<0.01	0.48	0.005	0.173	0.008	1.11	4.59	2.87
646833	Drill Core	1.01	<0.01	0.139	24.17	0.02	0.12	<0.01	0.01	<0.01	0.79	0.012	0.180	0.012	1.27	4.19	N.A.
646834	Drill Core	1.72	<0.01	0.149	24.13	0.02	0.15	0.01	<0.01	<0.01	1.02	0.022	0.163	0.014	1.30	2.89	N.A.
646835	Drill Core	3.52	<0.01	0.129	23.05	0.03	0.20	0.03	0.02	<0.01	0.39	0.004	0.104	0.005	0.92	2.42	N.A.
646836	Drill Core	3.75	<0.01	0.119	22.14	0.04	0.27	0.03	0.04	<0.01	0.42	0.003	0.106	0.005	0.83	2.25	N.A.
646837	Drill Core	3.24	<0.01	0.121	21.35	0.03	0.20	0.03	0.03	<0.01	1.66	0.034	0.127	0.017	1.28	2.18	N.A.
646838	Drill Core	2.49	<0.01	0.136	20.73	0.04	0.26	0.02	0.04	<0.01	1.22	0.021	0.115	0.011	1.04	1.88	N.A.
646839	Drill Core	1.95	<0.01	0.098	22.14	0.03	0.25	0.02	0.02	<0.01	0.59	0.009	0.152	0.008	0.73	1.85	N.A.
646840	Drill Core	2.65	<0.01	0.175	17.29	0.08	0.59	0.04	0.29	<0.01	1.12	0.019	0.103	0.010	0.83	0.82	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 17, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000760.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646841	Drill Core	10.33	4	<3	5	0.31	<0.001	0.004	<0.02	<0.01	<2	0.153	0.009	0.11	6.91	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646842	Drill Core	10.45	6	9	7	2.47	<0.001	0.029	<0.02	0.01	3	0.150	0.014	0.14	10.82	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
646843	Drill Core	9.70	3	10	7	0.26	<0.001	0.002	<0.02	<0.01	<2	0.218	0.011	0.12	6.95	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646844	Drill Core	9.96	2	3	5	0.53	<0.001	0.011	<0.02	<0.01	<2	0.244	0.013	0.12	7.28	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646845	Drill Core	10.68	4	6	7	0.38	<0.001	0.005	<0.02	<0.01	<2	0.218	0.011	0.14	8.01	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646846	Drill Core	10.56	3	9	6	0.38	<0.001	0.007	<0.02	<0.01	<2	0.179	0.011	0.13	8.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 17, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000760.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%		
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
646841	Drill Core	1.52	<0.01	0.113	20.16	0.21	1.50	0.02	0.74	<0.01	0.32	0.003	0.121	0.007	0.37	0.78	N.A.
646842	Drill Core	1.27	<0.01	0.106	16.63	0.31	1.91	0.05	1.27	<0.01	1.72	0.030	0.131	0.011	1.49	0.60	N.A.
646843	Drill Core	0.47	<0.01	0.112	23.35	0.09	0.71	<0.01	0.05	<0.01	0.22	<0.001	0.182	0.008	0.42	1.55	N.A.
646844	Drill Core	1.47	0.01	0.127	24.87	0.07	0.59	0.01	0.06	<0.01	0.43	0.010	0.187	0.009	0.69	1.95	N.A.
646845	Drill Core	1.58	<0.01	0.105	23.53	0.09	0.67	0.01	0.10	<0.01	0.33	0.004	0.169	0.007	0.64	1.90	N.A.
646846	Drill Core	1.39	<0.01	0.097	22.59	0.10	0.73	0.01	0.11	<0.01	0.30	0.006	0.156	0.009	0.48	1.44	N.A.

QUALITY CONTROL REPORT

SMI08000760.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
Pulp Duplicates																					
646815	Drill Core	10.93	22	139	140	2.99	<0.001	0.142	<0.02	<0.01	<2	0.716	0.025	0.13	11.27	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646815	QC	3.10																			
646818	Drill Core	10.91	24	136	160	1.27	<0.001	0.067	<0.02	<0.01	2	0.657	0.018	0.15	9.82	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646818	QC	18 126 160																			
646823	Drill Core	6.75	3	28	26	3.01	0.001	0.091	<0.02	<0.01	<2	0.332	0.030	0.13	12.48	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646823	QC	0.001 0.091 <0.02 <0.01 <2 0.333 0.031 0.13 12.67 <0.02 <0.01 <0.001 <0.01 <0.01 <0.01																			
646832	Drill Core	9.64	<2	6	5	0.50	<0.001	0.007	<0.02	<0.01	<2	0.226	0.011	0.13	6.90	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646832	QC																				
646846	Drill Core	10.56	3	9	6	0.38	<0.001	0.007	<0.02	<0.01	<2	0.179	0.011	0.13	8.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646846	QC																				
Core Reject Duplicates																					
646814	Drill Core	11.60	<2	53	37	2.24	<0.001	0.054	<0.02	<0.01	<2	0.293	0.018	0.15	10.78	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
DUP 646814	QC	5 66 47 2.56 <0.001 0.061 <0.02 <0.01 <2 0.355 0.020 0.13 10.01 <0.02 <0.01 <0.001 <0.01 <0.01 <0.01																			
Reference Materials																					
STD CDN-PGMS-14	Standard	235 103 419																			
STD CDN-PGMS-14	Standard	283 119 475																			
STD CDN-PGMS-14	Standard	216 111 404																			
STD CSC	Standard	4.17																			
STD CSC	Standard	4.20																			
STD FA10R	Standard	475 460 477																			
STD FA10R	Standard	494 487 496																			
STD FA10R	Standard	461 471 460																			
STD OREAS76A	Standard	16.03																			
STD OREAS76A	Standard	17.06																			
STD SF-3A_NI	Standard																				
STD SF-3A_NI	Standard																				
STD SF-3A_NI	Standard																				
STD SF-3T	Standard	0.031 0.779 0.94 1.09 57 0.357 0.018 0.43 8.05 <0.02 0.04 0.004 <0.01 <0.01 0.01																			

QUALITY CONTROL REPORT

SMI08000760.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG	
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%		
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
Pulp Duplicates																	
646815	Drill Core	1.28	<0.01	0.132	23.04	0.03	0.19	0.01	<0.01	<0.01	2.25	0.136	0.698	0.023	2.29	3.16	N.A.
REP 646815	QC										0.132	0.682	0.022	2.19	3.08		
646818	Drill Core	1.48	<0.01	0.168	23.91	0.02	0.15	0.01	<0.01	<0.01	1.07	0.068	0.566	0.014	1.68	2.87	N.A.
REP 646818	QC																
646823	Drill Core	1.15	<0.01	0.151	23.48	0.01	0.09	<0.01	<0.01	<0.01	2.25	0.091	0.303	0.026	1.80	2.69	N.A.
REP 646823	QC	1.16	<0.01	0.147	23.62	0.01	0.10	<0.01	<0.01	<0.01	2.33						
646832	Drill Core	2.23	<0.01	0.104	23.61	0.02	0.16	0.02	0.02	<0.01	0.48	0.005	0.173	0.008	1.11	4.59	2.87
REP 646832	QC										0.004	0.169	0.008	1.09	4.49		
646846	Drill Core	1.39	<0.01	0.097	22.59	0.10	0.73	0.01	0.11	<0.01	0.30	0.006	0.156	0.009	0.48	1.44	N.A.
REP 646846	QC										0.006	0.151	0.008	0.46	1.41		
Core Reject Duplicates																	
646814	Drill Core	1.87	<0.01	0.161	24.06	0.02	0.13	0.02	<0.01	<0.01	1.66	0.052	0.266	0.015	1.60	2.90	N.A.
DUP 646814	QC	1.79	<0.01	0.101	20.42	0.02	0.07	0.01	<0.01	<0.01	2.36	0.067	0.323	0.017	1.84	3.03	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																
STD OREAS76A	Standard																
STD SF-3A_NI	Standard										0.268	0.340	0.017	2.43	3.37		
STD SF-3A_NI	Standard										0.219	0.337	0.018	2.50	3.42		
STD SF-3A_NI	Standard										0.066	0.336	0.017	3.64	3.39		
STD SF-3T	Standard	4.09	0.06	0.018	4.62	0.21	5.51	2.13	2.51	<0.01	3.66						

QUALITY CONTROL REPORT

SMI08000760.1

		WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
STD SF-3T	Standard						0.031	0.768	0.94	1.07	53	0.352	0.018	0.42	7.99	<0.02	0.04	0.005	<0.01	<0.01	0.01
STD SF-3T	Standard						0.032	0.781	0.94	1.09	52	0.357	0.018	0.43	8.19	<0.02	0.04	0.004	<0.01	<0.01	0.01
STD SF-3T	Standard						0.032	0.789	0.95	1.09	52	0.360	0.018	0.44	8.21	<0.02	0.04	0.004	<0.01	<0.01	0.01
STD SF-3T	Standard						0.031	0.784	0.90	1.08	53	0.351	0.018	0.41	8.24	<0.02	0.04	0.005	<0.01	<0.01	0.01
STD SF-3T	Standard						0.032	0.782	0.92	1.08	52	0.356	0.018	0.42	8.24	<0.02	0.04	0.005	<0.01	<0.01	0.01
STD FA10R Expected			485	472	476																
STD CDN-PGMS-14			259	119	451																
STD SF-3T Expected						0.032	0.7723	0.961	1.0672	52	0.35	0.0181	0.432	8.33	0.004	0.044	0.00475	0.00111	0.00048	0.0143	
STD CSC Expected						4.19															
STD OREAS76A Expected						18															
STD SF-3A_NI Expected																					
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank																				
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank					<0.02															
BLK	Blank					<0.02															
BLK	Blank																				
Prep Wash																					
G1	Prep Blank	<0.01	<2	6	<2	<0.02	<0.001	<0.001	<0.02	0.01	<2	<0.001	<0.001	0.08	2.37	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank	<0.01	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.08	2.19	<0.02	0.07	<0.001	<0.01	<0.01	<0.01

QUALITY CONTROL REPORT

SMI08000760.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
STD SF-3T	Standard	4.01	0.06	0.017	4.55	0.20	5.39	2.04	2.49	<0.01	3.63						
STD SF-3T	Standard	4.11	0.06	0.021	4.62	0.20	5.47	2.06	2.46	<0.01	3.69						
STD SF-3T	Standard	4.12	0.06	0.021	4.63	0.20	5.50	2.07	2.48	<0.01	3.57						
STD SF-3T	Standard	4.03	0.05	0.018	4.63	0.19	5.37	2.05	2.47	<0.01	3.80						
STD SF-3T	Standard	4.05	0.05	0.018	4.64	0.19	5.42	2.06	2.48	<0.01	3.89						
STD FA10R Expected																	
STD CDN-PGMS-14																	
STD SF-3T Expected		4.1	0.06	0.02074	4.67	0.19	5.43	2.06	2.47	0.00043	3.5						
STD CSC Expected																	
STD OREAS76A Expected																	
STD SF-3A_NI Expected													0.3205				
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																
BLK	Blank																
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
Prep Wash																	
G1	Prep Blank	2.27	0.08	<0.001	0.66	0.23	7.75	2.48	3.06	<0.01	0.02	<0.001	<0.001	<0.001	0.16	0.04	N.A.
G1	Prep Blank	2.40	0.07	<0.001	0.66	0.22	8.27	2.67	3.02	<0.01	<0.01	<0.001	<0.001	<0.001	0.13	0.03	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Email Distribution List
 Receiving Lab: Canada-Smithers
 Received: August 25, 2008
 Report Date: September 18, 2008
 Page: 1 of 2

CERTIFICATE OF ANALYSIS

SMI08000806.1

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-258D
 P.O. Number
 Number of Samples: 14

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC: Email Distribution List

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	12	Crush split and pulverize drill core to 200 mesh		
3B	14	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	14	Analysis by Leco	0.1	Completed
7TD	14	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	14	Leached with H2O2 + NH4 citrate	1	Completed
Specific Gravity	1	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 18, 2008

Page: 2 of 2 Part 1

CERTIFICATE OF ANALYSIS

SMI08000806.1

Method	WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646847	Drill Core	10.64	<2	10	10	0.41	<0.001	0.007	<0.02	0.01	<2	0.186	0.011	0.14	8.35	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646848	Drill Core	10.78	<2	<3	3	0.36	<0.001	0.006	<0.02	<0.01	<2	0.187	0.011	0.12	8.12	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646849	Drill Core	10.76	<2	5	4	0.48	<0.001	0.008	<0.02	<0.01	<2	0.206	0.011	0.15	8.21	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646850	Rock Pulp	0.02	I.S.	I.S.	I.S.	0.47	<0.001	0.056	<0.02	0.02	4	0.231	0.011	0.10	8.53	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646851	Rock Pulp	0.02	I.S.	I.S.	I.S.	1.37	<0.001	0.031	<0.02	<0.01	<2	0.255	0.017	0.12	8.85	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646852	Drill Core	11.42	2	<3	<2	0.26	<0.001	0.004	<0.02	0.01	<2	0.216	0.011	0.13	7.80	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646853	Drill Core	10.70	2	<3	6	0.67	<0.001	0.013	<0.02	0.01	<2	0.233	0.012	0.14	8.32	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646854	Drill Core	11.20	<2	5	10	0.87	<0.001	0.016	<0.02	0.01	<2	0.211	0.012	0.14	8.60	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646855	Drill Core	10.41	<2	<3	8	1.82	<0.001	0.041	<0.02	<0.01	<2	0.151	0.012	0.14	8.39	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646856	Drill Core	10.42	3	<3	9	4.07	<0.001	0.066	<0.02	<0.01	<2	0.132	0.015	0.13	11.85	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646857	Drill Core	9.10	<2	<3	7	0.36	<0.001	0.006	<0.02	<0.01	<2	0.208	0.010	0.11	6.24	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646858	Drill Core	10.45	3	6	9	1.21	<0.001	0.009	<0.02	<0.01	<2	0.109	0.008	0.15	7.68	<0.02	<0.01	<0.001	<0.01	<0.01	0.04
646859	Drill Core	9.99	<2	<3	4	1.99	<0.001	0.011	<0.02	0.01	<2	0.066	0.008	0.20	10.29	<0.02	<0.01	<0.001	<0.01	<0.01	0.05
646860	Drill Core	1.48	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	1.08	<0.02	0.07	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: September 18, 2008

Page: 2 of 2 Part 2

CERTIFICATE OF ANALYSIS

SMI08000806.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S		Cu	Ni	Co	Fe	Mg	SG
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
646847	Drill Core	1.81	<0.01	0.084	21.90	0.08	0.67	0.01	0.09	<0.01	0.34	0.007	0.165	0.008	0.59	1.70	N.A.
646848	Drill Core	1.44	<0.01	0.067	22.38	0.10	0.80	0.01	0.14	<0.01	0.32	0.006	0.160	0.007	0.59	1.78	N.A.
646849	Drill Core	2.00	<0.01	0.085	22.06	0.10	0.70	0.01	0.11	<0.01	0.38	0.008	0.164	0.007	0.77	2.24	N.A.
646850	Rock Pulp	4.27	<0.01	0.853	13.29	0.18	3.83	0.33	0.11	<0.01	0.40	0.057	0.208	0.007	0.57	0.55	N.A.
646851	Rock Pulp	0.71	<0.01	0.161	23.37	0.02	0.31	<0.01	0.07	<0.01	1.13	0.033	0.252	0.013	1.34	3.85	N.A.
646852	Drill Core	0.73	<0.01	0.135	23.58	0.05	0.45	<0.01	0.06	<0.01	0.22	0.004	0.155	0.006	0.62	2.27	3.13
646853	Drill Core	3.13	<0.01	0.150	22.08	0.09	0.54	0.02	0.04	<0.01	0.54	0.013	0.179	0.007	0.76	1.93	N.A.
646854	Drill Core	3.25	<0.01	0.160	20.40	0.11	0.63	0.03	0.04	<0.01	0.69	0.016	0.183	0.009	0.94	2.00	N.A.
646855	Drill Core	7.10	<0.01	0.112	15.14	0.16	0.89	0.06	0.08	<0.01	1.29	0.044	0.154	0.011	1.14	0.66	N.A.
646856	Drill Core	5.01	<0.01	0.084	14.89	0.15	0.91	0.07	0.12	<0.01	2.92	0.073	0.133	0.014	2.94	0.79	N.A.
646857	Drill Core	1.45	<0.01	0.090	19.52	0.13	0.94	0.03	0.22	<0.01	0.30	0.006	0.196	0.008	0.45	0.92	N.A.
646858	Drill Core	5.66	<0.01	0.103	15.03	0.15	0.84	0.06	0.17	<0.01	0.83	0.010	0.102	0.007	0.79	0.88	N.A.
646859	Drill Core	5.26	<0.01	0.090	13.77	0.18	0.88	0.14	0.14	<0.01	1.43	0.012	0.059	0.007	1.52	0.62	N.A.
646860	Drill Core	1.84	<0.01	0.001	0.22	0.07	6.66	3.60	1.17	<0.01	<0.01	<0.001	<0.001	<0.001	0.12	0.04	N.A.

QUALITY CONTROL REPORT

SMI08000806.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
Pulp Duplicates																					
REP G1	QC																				
Reference Materials																					
STD CDN-PGMS-14	Standard	260	116	425																	
STD CSC	Standard				4.24																
STD FA10R	Standard	473	450	464																	
STD OREAS76A	Standard				17.18																
STD R3NI	Standard																				
STD SF-3T	Standard					0.032	0.775	0.93	1.09	52	0.347	0.018	0.42	8.13	<0.02	0.04	0.005	<0.01	<0.01	0.01	
STD SF-3T	Standard					0.032	0.780	0.94	1.10	53	0.348	0.018	0.43	8.15	<0.02	0.04	0.005	<0.01	<0.01	0.01	
STD SF-3T Expected						0.032	0.7723	0.961	1.0672	52	0.35	0.0181	0.432	8.33	0.004	0.044	0.00475	0.00111	0.00048	0.0143	
STD CSC Expected					4.19																
STD OREAS76A Expected					18																
STD FA10R Expected		485	472	476																	
STD CDN-PGMS-14		259	119	451																	
STD R3NI Expected																					
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	
BLK	Blank				<0.02																
BLK	Blank	<2	<3	<2																	
BLK	Blank	<2	<3	<2																	
BLK	Blank																				
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2	<0.02	<0.001	0.001	<0.02	<0.01	<2	<0.001	<0.001	0.08	2.43	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank	<0.01	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.45	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank																				

QUALITY CONTROL REPORT

SMI08000806.1

Method		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
Unit		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
Pulp Duplicates																	
REP G1	QC											<0.001	<0.001	<0.001	0.06	0.06	
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																
STD R3NI	Standard											0.748	0.393	0.054	4.13	0.15	
STD SF-3T	Standard	4.04	0.05	0.020	4.53	0.20	5.39	2.05	2.45	<0.01	3.79						
STD SF-3T	Standard	4.03	0.06	0.020	4.56	0.20	5.43	2.04	2.48	<0.01	3.92						
STD SF-3T Expected		4.1	0.06	0.02074	4.67	0.19	5.43	2.06	2.47	0.00043	3.5						
STD CSC Expected																	
STD OREAS76A Expected																	
STD FA10R Expected																	
STD CDN-PGMS-14																	
STD R3NI Expected												0.42					
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
Prep Wash																	
G1	Prep Blank	2.66	0.07	<0.001	0.71	0.25	7.29	2.71	2.98	<0.01	<0.01						N.A.
G1	Prep Blank	2.59	0.06	<0.001	0.67	0.24	6.92	2.60	2.98	<0.01	<0.01	<0.001	<0.001	<0.001	0.06	0.06	N.A.
G1	Prep Blank											<0.001	<0.001	<0.001	0.06	0.06	

Hole 08-259



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Email Distribution List
 Receiving Lab: Canada-Smithers
 Received: September 02, 2008
 Report Date: October 30, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000853.1

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-259A
 P.O. Number
 Number of Samples: 52

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC: Email Distribution List

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	48	Crush split and pulverize drill core to 200 mesh		
3B	48	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	52	Analysis by Leco	0.1	Completed
7TD	52	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	52	Leached with H2O2 + NH4 citrate	1	Completed
Specific Gravity	3	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.
 All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.
 "**" asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 30, 2008

Page: 2 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000853.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646861	Drill Core	2.49	<2	21	31	0.72	<0.001	0.015	<0.02	<0.01	<2	0.345	0.021	0.12	8.38	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646862	Drill Core	10.65	<2	14	20	0.21	<0.001	0.013	<0.02	<0.01	<2	0.295	0.013	0.11	6.56	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646863	Drill Core	9.37	<2	18	19	0.19	<0.001	0.027	<0.02	<0.01	<2	0.247	0.012	0.10	6.95	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646864	Drill Core	9.78	<2	5	3	0.09	<0.001	0.004	<0.02	<0.01	<2	0.255	0.011	0.10	6.19	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646865	Drill Core	10.39	<2	4	3	0.03	<0.001	0.001	<0.02	<0.01	<2	0.246	0.012	0.10	5.51	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646866	Drill Core	11.15	<2	<3	8	0.11	<0.001	0.005	<0.02	<0.01	<2	0.241	0.012	0.10	6.00	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646867	Drill Core	9.90	<2	21	24	0.39	<0.001	0.015	<0.02	<0.01	<2	0.322	0.014	0.10	5.83	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646868	Drill Core	9.79	<2	12	19	0.21	<0.001	0.008	<0.02	<0.01	<2	0.265	0.013	0.10	5.46	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646869	Drill Core	10.38	<2	5	9	0.16	<0.001	0.005	<0.02	<0.01	<2	0.209	0.010	0.11	5.64	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646870	Drill Core	6.62	2	20	33	0.47	<0.001	0.015	<0.02	<0.01	<2	0.309	0.013	0.12	6.39	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646871	Drill Core	3.34	<2	4	5	1.86	<0.001	0.041	<0.02	<0.01	<2	0.123	0.021	0.09	9.77	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646872	Drill Core	10.04	<2	<3	5	3.20	0.001	0.050	<0.02	<0.01	<2	0.117	0.018	0.10	10.81	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646873	Drill Core	9.49	<2	6	5	0.92	<0.001	0.020	<0.02	<0.01	<2	0.161	0.010	0.07	6.31	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646874	Drill Core	10.03	<2	20	23	0.37	<0.001	0.008	<0.02	<0.01	<2	0.250	0.011	0.09	4.86	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646875	Rock Pulp	0.04	I.S.	I.S.	I.S.	0.46	<0.001	0.052	<0.02	0.02	<2	0.215	0.011	0.11	8.03	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646876	Rock Pulp	0.02	I.S.	I.S.	I.S.	4.19	<0.001	0.047	<0.02	<0.01	<2	0.407	0.027	0.12	12.53	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646877	Drill Core	8.88	<2	7	7	0.29	<0.001	0.008	<0.02	<0.01	<2	0.231	0.010	0.09	4.71	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646878	Drill Core	10.04	<2	18	22	0.42	<0.001	0.011	<0.02	<0.01	<2	0.275	0.012	0.09	4.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646879	Drill Core	9.91	<2	12	14	0.17	<0.001	0.005	<0.02	<0.01	<2	0.265	0.010	0.08	4.61	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646880A	Drill Core	9.49	<2	18	23	0.23	<0.001	0.007	<0.02	<0.01	<2	0.299	0.012	0.08	4.98	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646880B	Client Dup		<2	18	24	0.25	<0.001	0.007	<0.02	<0.01	<2	0.312	0.012	0.08	5.15	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646881	Drill Core	9.42	<2	14	15	0.32	<0.001	0.008	<0.02	<0.01	<2	0.307	0.014	0.10	5.43	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646882	Drill Core	8.57	<2	10	14	0.41	<0.001	0.009	<0.02	<0.01	<2	0.246	0.013	0.09	6.30	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646883	Drill Core	9.03	<2	25	21	1.27	<0.001	0.022	<0.02	<0.01	<2	0.233	0.012	0.07	6.90	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646884	Drill Core	9.98	<2	15	20	1.42	<0.001	0.028	<0.02	<0.01	<2	0.197	0.015	0.09	8.09	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646885	Drill Core	8.88	<2	5	5	1.91	0.001	0.026	<0.02	<0.01	<2	0.128	0.009	0.07	5.91	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646886	Drill Core	5.40	<2	7	6	1.09	<0.001	0.014	<0.02	0.01	<2	0.196	0.009	0.09	5.16	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646887	Drill Core	4.72	<2	3	11	5.19	0.004	0.039	<0.02	0.02	<2	0.044	0.008	0.16	12.67	<0.02	0.04	<0.001	<0.01	<0.01	0.04
646888	Drill Core	10.50	<2	4	5	1.46	0.003	0.015	<0.02	0.02	<2	0.017	0.003	0.20	7.28	<0.02	0.02	<0.001	<0.01	<0.01	0.04
646889	Drill Core	10.42	<2	<3	6	2.54	0.002	0.027	<0.02	0.02	<2	0.018	0.003	0.16	7.31	<0.02	0.06	<0.001	<0.01	<0.01	0.04



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 30, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000853.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
646861	Drill Core	0.64	<0.01	0.273	26.64	0.01	0.10	<0.01	0.01	<0.01	0.70	0.014	0.233	0.010	0.84	1.62	N.A.
646862	Drill Core	0.73	<0.01	0.180	25.73	0.01	0.10	0.01	<0.01	<0.01	0.19	0.012	0.117	0.004	0.60	1.84	N.A.
646863	Drill Core	0.79	<0.01	0.282	24.10	0.02	0.18	0.01	<0.01	<0.01	0.21	0.024	0.152	0.006	0.53	2.15	N.A.
646864	Drill Core	0.36	<0.01	0.082	25.65	0.02	0.18	<0.01	0.01	<0.01	0.10	0.003	0.093	0.004	0.49	2.09	N.A.
646865	Drill Core	0.56	<0.01	0.113	25.83	0.03	0.23	<0.01	0.11	<0.01	0.03	0.001	0.043	0.002	0.56	1.99	N.A.
646866	Drill Core	0.75	<0.01	0.137	25.89	0.05	0.33	<0.01	0.13	<0.01	0.15	0.004	0.077	0.004	0.53	1.98	N.A.
646867	Drill Core	1.08	<0.01	0.094	23.85	0.05	0.34	0.01	0.12	<0.01	0.42	0.014	0.234	0.008	0.63	2.00	N.A.
646868	Drill Core	1.09	<0.01	0.082	24.31	0.06	0.49	0.01	0.18	<0.01	0.25	0.007	0.160	0.006	0.38	1.50	N.A.
646869	Drill Core	2.09	0.01	0.131	22.45	0.07	0.66	0.02	0.16	<0.01	0.21	0.005	0.126	0.005	0.35	1.17	N.A.
646870	Drill Core	1.35	<0.01	0.078	22.32	0.05	0.53	0.01	0.14	<0.01	0.49	0.013	0.223	0.007	0.52	1.45	N.A.
646871	Drill Core	2.32	0.01	0.049	19.53	0.08	0.71	0.01	0.16	<0.01	1.39	0.036	0.113	0.017	0.39	0.71	N.A.
646872	Drill Core	1.51	<0.01	0.094	20.21	0.08	0.65	0.01	0.16	<0.01	2.68	0.048	0.114	0.015	0.49	0.98	3.02
646873	Drill Core	1.76	<0.01	0.100	20.19	0.07	0.87	0.01	0.15	<0.01	0.85	0.016	0.145	0.008	0.38	1.02	N.A.
646874	Drill Core	2.56	0.02	0.115	22.18	0.08	0.85	0.02	0.22	<0.01	0.41	0.007	0.177	0.007	0.33	0.97	N.A.
646875	Rock Pulp	4.19	<0.01	0.975	13.17	0.18	3.86	0.32	0.11	<0.01	0.48	0.052	0.170	0.006	0.46	0.69	N.A.
646876	Rock Pulp	1.12	<0.01	0.177	21.44	0.02	0.28	0.03	0.10	<0.01	3.02	0.042	0.350	0.020	0.94	1.31	N.A.
646877	Drill Core	1.14	<0.01	0.086	23.15	0.05	0.79	<0.01	0.15	<0.01	0.33	0.006	0.168	0.006	0.41	1.58	N.A.
646878	Drill Core	1.44	0.01	0.117	23.44	0.06	0.89	<0.01	0.17	<0.01	0.45	0.009	0.190	0.007	0.38	1.20	N.A.
646879	Drill Core	0.61	<0.01	0.107	24.52	0.04	0.68	<0.01	0.13	<0.01	0.21	0.003	0.154	0.005	0.35	1.28	N.A.
646880A	Drill Core	1.02	0.01	0.059	23.41	0.06	0.69	<0.01	0.12	<0.01	0.28	0.005	0.214	0.007	0.40	1.36	N.A.
646880B	Client Dup	0.97	0.01	0.065	24.09	0.06	0.70	<0.01	0.12	<0.01	0.30	0.005	0.222	0.008	0.40	1.38	N.A.
646881	Drill Core	0.80	0.01	0.261	24.03	0.05	0.69	<0.01	0.12	<0.01	0.36	0.005	0.234	0.009	0.42	1.42	N.A.
646882	Drill Core	2.69	0.02	0.117	21.80	0.08	0.90	0.02	0.16	<0.01	0.61	0.007	0.179	0.008	0.37	1.17	2.93
646883	Drill Core	1.82	0.03	0.069	20.80	0.08	0.96	<0.01	0.08	<0.01	1.34	0.017	0.197	0.009	0.56	1.12	N.A.
646884	Drill Core	2.48	<0.01	0.072	20.76	0.07	0.79	0.01	0.13	<0.01	1.46	0.022	0.168	0.011	0.41	0.91	N.A.
646885	Drill Core	4.31	0.03	0.073	18.31	0.08	0.97	0.02	0.14	<0.01	1.89	0.021	0.094	0.006	0.42	0.65	N.A.
646886	Drill Core	3.11	0.04	0.091	20.49	0.09	1.16	0.01	0.20	<0.01	1.24	0.011	0.132	0.006	0.49	1.02	N.A.
646887	Drill Core	6.82	0.08	0.022	6.79	0.30	5.06	1.17	1.46	<0.01	4.58	0.036	0.018	0.003	0.50	0.35	N.A.
646888	Drill Core	6.55	0.06	0.024	5.60	0.36	5.59	2.60	1.49	<0.01	1.47	0.014	0.008	0.001	0.36	0.33	N.A.
646889	Drill Core	5.99	0.10	0.008	3.36	0.35	6.72	2.87	1.44	<0.01	2.31	0.025	0.008	0.001	0.23	0.08	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 30, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000853.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646890	Drill Core	1.69	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	1.09	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
646891	Drill Core	8.83	<2	4	7	1.83	0.001	0.035	<0.02	0.02	<2	0.021	0.006	0.16	8.64	<0.02	0.03	<0.001	<0.01	<0.01	0.06
646892	Drill Core	11.64	<2	12	16	1.84	0.002	0.055	<0.02	0.02	<2	0.018	0.008	0.18	12.35	<0.02	<0.01	<0.001	<0.01	<0.01	0.07
646893	Drill Core	12.57	<2	10	25	3.38	0.002	0.060	<0.02	0.02	<2	0.023	0.008	0.17	12.37	<0.02	<0.01	<0.001	<0.01	<0.01	0.08
646894	Drill Core	12.78	<2	43	31	3.31	0.002	0.045	<0.02	<0.01	<2	0.043	0.009	0.15	13.13	<0.02	<0.01	<0.001	<0.01	<0.01	0.07
646895	Drill Core	11.50	<2	<3	13	2.62	<0.001	0.038	<0.02	<0.01	<2	0.079	0.011	0.15	10.77	<0.02	<0.01	<0.001	<0.01	<0.01	0.06
646896	Drill Core	11.94	<2	<3	8	2.65	<0.001	0.028	<0.02	<0.01	<2	0.042	0.009	0.17	10.98	<0.02	<0.01	<0.001	<0.01	<0.01	0.05
646897	Drill Core	10.75	<2	3	11	3.09	<0.001	0.041	<0.02	<0.01	<2	0.013	0.009	0.17	12.79	<0.02	0.01	<0.001	<0.01	<0.01	0.07
646898	Drill Core	11.72	<2	<3	19	1.85	0.001	0.029	<0.02	0.01	<2	0.032	0.007	0.17	9.83	<0.02	0.27	<0.001	<0.01	<0.01	0.04
646899	Drill Core	9.78	<2	<3	7	2.45	0.003	0.033	<0.02	0.01	<2	0.141	0.009	0.13	7.38	<0.02	0.01	<0.001	<0.01	<0.01	0.03
646900	Rock Pulp	0.04	I.S.	I.S.	I.S.	0.45	<0.001	0.054	<0.02	0.02	<2	0.237	0.012	0.11	8.91	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646901	Rock Pulp	0.02	I.S.	I.S.	I.S.	1.38	<0.001	0.030	<0.02	<0.01	<2	0.250	0.016	0.12	8.67	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646902	Drill Core	9.01	<2	<3	<2	0.74	<0.001	0.041	<0.02	<0.01	<2	0.233	0.016	0.12	9.19	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646903	Drill Core	9.61	<2	41	51	1.05	<0.001	0.029	<0.02	<0.01	<2	0.290	0.021	0.13	8.44	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646904	Drill Core	9.63	<2	51	60	1.03	<0.001	0.029	<0.02	<0.01	<2	0.293	0.020	0.11	8.52	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646905	Drill Core	9.90	<2	13	33	0.56	<0.001	0.056	<0.02	<0.01	<2	0.278	0.014	0.11	6.86	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646906	Drill Core	9.69	<2	12	33	0.54	<0.001	0.030	<0.02	<0.01	<2	0.318	0.015	0.09	7.94	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646907	Drill Core	9.19	<2	8	14	0.81	<0.001	0.057	<0.02	<0.01	<2	0.260	0.015	0.11	7.81	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646908	Drill Core	10.85	<2	82	<2	1.30	<0.001	0.074	<0.02	<0.01	<2	0.238	0.018	0.15	9.60	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646909	Drill Core	10.95	<2	22	40	2.23	<0.001	0.045	<0.02	<0.01	<2	0.368	0.022	0.12	9.61	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646910A	Drill Core	10.88	3	41	70	1.51	<0.001	0.036	<0.02	<0.01	<2	0.458	0.017	0.13	7.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646910B	Client Dup		4	66	69	1.46	<0.001	0.033	<0.02	<0.01	<2	0.448	0.017	0.12	7.72	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 30, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000853.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
646890	Drill Core	2.10	0.02	0.001	0.20	0.07	8.04	3.75	1.15	<0.01	0.02	<0.001	<0.001	<0.001	0.03	0.02	N.A.
646891	Drill Core	10.14	0.05	0.060	7.58	0.21	3.11	0.78	1.38	<0.01	1.79	0.030	0.011	0.003	0.26	0.08	N.A.
646892	Drill Core	12.53	0.03	0.042	7.66	0.50	3.27	0.09	0.59	<0.01	1.91	0.050	0.009	0.003	0.41	0.15	3.23
646893	Drill Core	15.07	0.06	0.030	6.86	0.29	1.99	0.04	0.09	<0.01	2.80	0.060	0.010	0.003	0.53	0.11	N.A.
646894	Drill Core	14.30	0.10	0.028	7.55	0.30	2.46	0.05	0.20	<0.01	2.58	0.047	0.024	0.005	0.45	0.17	N.A.
646895	Drill Core	11.57	0.09	0.048	9.33	0.35	2.32	0.08	0.81	<0.01	1.86	0.039	0.059	0.008	0.68	0.30	N.A.
646896	Drill Core	11.64	0.10	0.080	9.37	0.49	2.69	0.10	0.33	<0.01	2.09	0.029	0.027	0.004	0.62	0.36	N.A.
646897	Drill Core	12.38	0.17	0.016	6.61	0.64	3.20	0.26	1.02	<0.01	2.25	0.043	0.004	0.003	0.58	0.10	N.A.
646898	Drill Core	11.21	0.07	0.034	5.79	0.27	4.17	0.38	1.70	<0.01	1.45	0.030	0.020	0.004	0.41	0.11	N.A.
646899	Drill Core	7.02	<0.01	0.101	14.74	0.08	0.54	0.09	0.22	<0.01	2.26	0.032	0.117	0.007	0.52	0.67	N.A.
646900	Rock Pulp	4.29	<0.01	1.094	13.78	0.18	4.02	0.33	0.11	<0.01	0.44	0.055	0.176	0.007	0.41	0.51	N.A.
646901	Rock Pulp	0.70	<0.01	0.157	24.75	0.02	0.30	<0.01	0.09	<0.01	1.09	0.029	0.213	0.012	0.84	2.15	N.A.
646902	Drill Core	0.70	<0.01	0.211	22.97	0.02	0.14	<0.01	0.05	<0.01	0.65	0.036	0.211	0.014	0.71	2.54	N.A.
646903	Drill Core	0.17	<0.01	0.096	25.32	<0.01	0.11	<0.01	<0.01	<0.01	0.90	0.024	0.267	0.018	0.81	2.52	N.A.
646904	Drill Core	0.05	<0.01	0.117	25.52	<0.01	0.10	<0.01	<0.01	<0.01	0.89	0.026	0.265	0.017	0.80	2.66	N.A.
646905	Drill Core	0.63	<0.01	0.156	25.22	0.01	0.13	<0.01	<0.01	<0.01	0.51	0.056	0.263	0.012	0.75	2.68	N.A.
646906	Drill Core	0.05	<0.01	0.155	24.67	0.01	0.13	<0.01	<0.01	<0.01	0.54	0.028	0.297	0.013	0.79	3.11	N.A.
646907	Drill Core	0.06	<0.01	0.166	25.89	<0.01	0.10	<0.01	<0.01	<0.01	0.72	0.049	0.227	0.012	0.74	2.59	N.A.
646908	Drill Core	0.10	<0.01	0.280	25.01	<0.01	0.07	<0.01	<0.01	<0.01	1.12	0.065	0.216	0.015	0.77	2.61	N.A.
646909	Drill Core	0.05	<0.01	0.078	25.64	<0.01	0.03	<0.01	<0.01	<0.01	1.75	0.044	0.338	0.019	0.80	1.76	N.A.
646910A	Drill Core	0.04	<0.01	0.113	26.62	<0.01	0.06	<0.01	<0.01	<0.01	1.27	0.034	0.412	0.015	0.91	2.22	N.A.
646910B	Client Dup	0.04	<0.01	0.102	25.31	<0.01	0.05	<0.01	<0.01	<0.01	1.25	0.032	0.418	0.015	0.94	2.33	N.A.

QUALITY CONTROL REPORT

SMI08000853.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
Pulp Duplicates																					
646872	Drill Core	10.04	<2	<3	5	3.20	0.001	0.050	<0.02	<0.01	<2	0.117	0.018	0.10	10.81	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
REP 646872	QC																				
646874	Drill Core	10.03	<2	20	23	0.37	<0.001	0.008	<0.02	<0.01	<2	0.250	0.011	0.09	4.86	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646874	QC																				
646876	Rock Pulp	0.02	I.S.	I.S.	I.S.	4.19	<0.001	0.047	<0.02	<0.01	<2	0.407	0.027	0.12	12.53	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646876	QC					<0.001	0.046	<0.02	<0.01	<2	0.402	0.027	0.12	12.35	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
646880A	Drill Core	9.49	<2	18	23	0.23	<0.001	0.007	<0.02	<0.01	<2	0.299	0.012	0.08	4.98	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646880A	QC																				
646885	Drill Core	8.88	<2	5	5	1.91	0.001	0.026	<0.02	<0.01	<2	0.128	0.009	0.07	5.91	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
REP 646885	QC		3	6	4																
646888	Drill Core	10.50	<2	4	5	1.46	0.003	0.015	<0.02	0.02	<2	0.017	0.003	0.20	7.28	<0.02	0.02	<0.001	<0.01	<0.01	0.04
REP 646888	QC					1.49															
646891	Drill Core	8.83	<2	4	7	1.83	0.001	0.035	<0.02	0.02	<2	0.021	0.006	0.16	8.64	<0.02	0.03	<0.001	<0.01	<0.01	0.06
REP 646891	QC																				
646893	Drill Core	12.57	<2	10	25	3.38	0.002	0.060	<0.02	0.02	<2	0.023	0.008	0.17	12.37	<0.02	<0.01	<0.001	<0.01	<0.01	0.08
REP 646893	QC																				
646895	Drill Core	11.50	<2	<3	13	2.62	<0.001	0.038	<0.02	<0.01	<2	0.079	0.011	0.15	10.77	<0.02	<0.01	<0.001	<0.01	<0.01	0.06
REP 646895	QC		<2	16	16																
646899	Drill Core	9.78	<2	<3	7	2.45	0.003	0.033	<0.02	0.01	<2	0.141	0.009	0.13	7.38	<0.02	0.01	<0.001	<0.01	<0.01	0.03
REP 646899	QC					0.003	0.033	<0.02	0.01	<2	0.139	0.008	0.13	7.23	<0.02	0.01	<0.001	<0.01	<0.01	<0.01	0.03
Core Reject Duplicates																					
646878	Drill Core	10.04	<2	18	22	0.42	<0.001	0.011	<0.02	<0.01	<2	0.275	0.012	0.09	4.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
DUP 646878	QC		<2	18	21	0.43	<0.001	0.010	<0.02	<0.01	<2	0.268	0.012	0.09	4.86	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
Reference Materials																					
STD CDN-PGMS-14	Standard		250	103	433																
STD CDN-PGMS-14	Standard		228	96	404																
STD CSC	Standard					4.07															
STD CSC	Standard					4.24															

QUALITY CONTROL REPORT

SMI08000853.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG	
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%		
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
Pulp Duplicates																	
646872	Drill Core	1.51	<0.01	0.094	20.21	0.08	0.65	0.01	0.16	<0.01	2.68	0.048	0.114	0.015	0.49	0.98	3.02
REP 646872	QC										0.050	0.116	0.016	0.57	1.08		
646874	Drill Core	2.56	0.02	0.115	22.18	0.08	0.85	0.02	0.22	<0.01	0.41	0.007	0.177	0.007	0.33	0.97	N.A.
REP 646874	QC										0.006	0.177	0.006	0.32	1.08		
646876	Rock Pulp	1.12	<0.01	0.177	21.44	0.02	0.28	0.03	0.10	<0.01	3.02	0.042	0.350	0.020	0.94	1.31	N.A.
REP 646876	QC	1.11	<0.01	0.170	20.82	0.02	0.28	0.03	0.10	<0.01	2.99						
646880A	Drill Core	1.02	0.01	0.059	23.41	0.06	0.69	<0.01	0.12	<0.01	0.28	0.005	0.214	0.007	0.40	1.36	N.A.
REP 646880A	QC										0.006	0.236	0.009	0.50	1.63		
646885	Drill Core	4.31	0.03	0.073	18.31	0.08	0.97	0.02	0.14	<0.01	1.89	0.021	0.094	0.006	0.42	0.65	N.A.
REP 646885	QC																
646888	Drill Core	6.55	0.06	0.024	5.60	0.36	5.59	2.60	1.49	<0.01	1.47	0.014	0.008	0.001	0.36	0.33	N.A.
REP 646888	QC																
646891	Drill Core	10.14	0.05	0.060	7.58	0.21	3.11	0.78	1.38	<0.01	1.79	0.030	0.011	0.003	0.26	0.08	N.A.
REP 646891	QC										0.031	0.012	0.003	0.77	0.31		
646893	Drill Core	15.07	0.06	0.030	6.86	0.29	1.99	0.04	0.09	<0.01	2.80	0.060	0.010	0.003	0.53	0.11	N.A.
REP 646893	QC										0.060	0.010	0.003	0.49	0.11		
646895	Drill Core	11.57	0.09	0.048	9.33	0.35	2.32	0.08	0.81	<0.01	1.86	0.039	0.059	0.008	0.68	0.30	N.A.
REP 646895	QC																
646899	Drill Core	7.02	<0.01	0.101	14.74	0.08	0.54	0.09	0.22	<0.01	2.26	0.032	0.117	0.007	0.52	0.67	N.A.
REP 646899	QC	6.81	<0.01	0.098	14.50	0.08	0.52	0.08	0.21	<0.01	2.21						
Core Reject Duplicates																	
646878	Drill Core	1.44	0.01	0.117	23.44	0.06	0.89	<0.01	0.17	<0.01	0.45	0.009	0.190	0.007	0.38	1.20	N.A.
DUP 646878	QC	1.18	0.01	0.110	23.30	0.05	0.84	<0.01	0.16	<0.01	0.41	0.008	0.176	0.007	0.34	1.10	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard																
STD CSC	Standard																

QUALITY CONTROL REPORT

SMI08000853.1

		WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
STD CSC	Standard					4.35															
STD CSC	Standard					4.26															
STD FA10R	Standard		468	419	472																
STD FA10R	Standard		425	421	445																
STD FA10R	Standard		462	450	471																
STD FA10R	Standard		482	458	492																
STD OREAS76A	Standard					17.48															
STD OREAS76A	Standard					17.79															
STD OREAS76A	Standard					17.20															
STD OREAS76A	Standard					17.76															
STD R4T	Standard					0.063	0.520	1.56	3.55	90	0.364	0.042	0.09	24.93	<0.02	0.02	0.018	0.01	<0.01	0.02	
STD R4T	Standard					0.061	0.507	1.56	3.50	88	0.357	0.040	0.09	24.24	<0.02	0.02	0.018	<0.01	<0.01	0.02	
STD R4T	Standard					0.061	0.504	1.55	3.40	87	0.355	0.040	0.09	24.12	<0.02	0.02	0.018	0.01	<0.01	0.01	
STD SF-3A_NI	Standard																				
STD SF-3A_NI	Standard																				
STD SF-3A	Standard																				
STD SF-3T	Standard					0.032	0.786	0.95	1.11	52	0.355	0.018	0.43	8.39	<0.02	0.04	0.004	<0.01	<0.01	0.01	
STD SF-3T	Standard					0.031	0.762	0.94	1.08	53	0.342	0.018	0.43	8.08	<0.02	0.04	0.005	<0.01	<0.01	0.01	
STD SF-3T	Standard					0.031	0.773	0.87	1.07	52	0.352	0.018	0.42	8.23	<0.02	0.04	0.004	<0.01	<0.01	0.01	
STD SF-3T Expected						0.032	0.7723	0.961	1.0672	52	0.35	0.0181	0.432	8.33	0.004	0.044	0.00475	0.00111	0.00048	0.0143	
STD R4T Expected						0.062	0.502	1.518	3.376	86	0.348	0.039	0.086	24.07	0.0087	0.0185	0.018	0.0138	0.0018	0.016	
STD CDN-PGMS-14			259	119	451																
STD FA10R Expected			485	472	476																
STD CSC Expected						4.25															
STD OREAS76A Expected						18															
STD SF-3A Expected																					
STD SF-3A_NI Expected																					
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01

QUALITY CONTROL REPORT

SMI08000853.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
STD CSC	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																
STD OREAS76A	Standard																
STD OREAS76A	Standard																
STD OREAS76A	Standard																
STD R4T	Standard	2.21	0.05	0.018	1.43	0.21	4.01	0.92	1.19	<0.01	13.15						
STD R4T	Standard	2.20	0.04	0.019	1.41	0.20	3.97	0.92	1.16	<0.01	12.50						
STD R4T	Standard	2.15	0.04	0.018	1.40	0.20	3.93	0.90	1.17	<0.01	11.47						
STD SF-3A_NI	Standard											0.795	0.323	0.015	1.62	2.45	
STD SF-3A_NI	Standard											0.733	0.318	0.015	1.77	2.38	
STD SF-3A	Standard											0.803	0.327	0.015	1.64	2.43	
STD SF-3T	Standard	4.10	0.05	0.014	4.65	0.20	5.48	2.05	2.49	<0.01	4.39						
STD SF-3T	Standard	4.04	0.06	0.016	4.54	0.19	5.36	2.05	2.44	<0.01	4.16						
STD SF-3T	Standard	4.02	0.05	0.017	4.57	0.19	5.43	2.05	2.47	<0.01	3.96						
STD SF-3T Expected		4.1	0.06	0.02074	4.67	0.19	5.43	2.06	2.47	0.00043	3.5						
STD R4T Expected		2.166	0.045	0.018	1.384		3.897	0.9	1.153	0.00016							
STD CDN-PGMS-14																	
STD FA10R Expected																	
STD CSC Expected																	
STD OREAS76A Expected																	
STD SF-3A Expected												0.7705	0.3365	0.0183	7.91	4.27	
STD SF-3A_NI Expected												0.3205					
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						

QUALITY CONTROL REPORT

SMI08000853.1

		WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank					<0.02															
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank					<0.02															
BLK	Blank					<0.02															
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank					<0.02															
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
Prep Wash																					
G1	Prep Blank	<0.01	2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.31	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank	<0.01	<2	<3	<2	0.03	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.08	2.41	<0.02	0.07	<0.001	<0.01	<0.01	<0.01

QUALITY CONTROL REPORT

SMI08000853.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NIS	8NIS	8NIS	8NIS	8NIS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
BLK	Blank																
BLK	Blank																
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	0.10	<0.01	<0.01						
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
Prep Wash																	
G1	Prep Blank	2.44	0.08	<0.001	0.70	0.24	7.55	2.58	2.98	<0.01	0.02	<0.001	<0.001	<0.001	0.05	0.03	N.A.
G1	Prep Blank	2.40	0.09	<0.001	0.67	0.24	7.49	2.56	3.04	<0.01	0.02	<0.001	<0.001	<0.001	0.03	0.01	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Email Distribution List
 Receiving Lab: Canada-Smithers
 Received: August 25, 2008
 Report Date: October 17, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000807.1

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-259B
 P.O. Number
 Number of Samples: 37

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC: Email Distribution List

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	35	Crush split and pulverize drill core to 200 mesh		
3B	37	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	37	Analysis by Leco	0.1	Completed
7TD	37	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	37	Leached with H2O2 + NH4 citrate	1	Completed
Specific Gravity	2	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. ** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 17, 2008

Page: 2 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000807.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646911	Drill Core	10.99	4	48	64	0.84	<0.001	0.020	<0.02	<0.01	2	0.521	0.017	0.13	7.61	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646912	Drill Core	10.02	3	44	61	0.95	<0.001	0.031	<0.02	<0.01	2	0.667	0.016	0.14	7.74	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646913	Drill Core	9.27	8	131	189	1.08	<0.001	0.048	<0.02	<0.01	<2	0.672	0.022	0.13	8.37	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646914	Drill Core	9.90	11	49	62	0.66	<0.001	0.018	<0.02	<0.01	<2	0.198	0.010	0.07	6.41	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646915	Drill Core	9.45	6	11	15	0.78	<0.001	0.036	<0.02	<0.01	<2	0.227	0.016	0.14	7.60	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646916	Drill Core	8.99	24	5	15	0.76	<0.001	0.068	<0.02	<0.01	<2	0.195	0.013	0.09	7.64	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646917	Drill Core	9.68	8	14	16	1.27	<0.001	0.030	<0.02	<0.01	<2	0.329	0.021	0.13	8.30	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646918	Drill Core	10.33	7	23	27	1.47	<0.001	0.061	<0.02	<0.01	<2	0.331	0.019	0.13	7.65	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646919	Drill Core	9.73	<2	10	10	1.04	<0.001	0.022	<0.02	<0.01	<2	0.226	0.021	0.12	9.43	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646920	Drill Core	1.36	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.003	<0.001	0.07	1.12	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
646921	Drill Core	10.51	2	10	18	1.33	<0.001	0.029	<0.02	<0.01	<2	0.270	0.021	0.13	9.62	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646922	Drill Core	9.19	2	8	11	0.84	<0.001	0.015	<0.02	<0.01	<2	0.241	0.017	0.12	8.55	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646923	Drill Core	10.11	<2	8	8	0.77	<0.001	0.016	<0.02	<0.01	<2	0.214	0.014	0.12	8.36	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646924	Drill Core	10.49	2	10	12	1.04	<0.001	0.029	<0.02	<0.01	<2	0.176	0.014	0.12	8.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646925	Rock Pulp	0.02	<2	17	<2	1.33	<0.001	0.031	<0.02	<0.01	<2	0.255	0.017	0.11	8.80	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646926	Rock Pulp	0.02	<2	15	<2	0.40	<0.001	0.056	<0.02	0.02	<2	0.233	0.012	0.11	8.91	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646927	Drill Core	8.59	<2	9	10	2.11	<0.001	0.049	<0.02	<0.01	<2	0.115	0.023	0.10	10.88	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646928	Drill Core	10.61	<2	5	8	1.88	<0.001	0.044	<0.02	<0.01	<2	0.201	0.028	0.15	10.89	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646929	Drill Core	10.45	4	22	20	1.81	<0.001	0.089	<0.02	<0.01	<2	0.365	0.020	0.13	9.62	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646930	Drill Core	10.33	2	15	13	1.56	<0.001	0.069	<0.02	0.01	<2	0.222	0.023	0.12	10.19	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646931	Drill Core	9.65	<2	8	7	0.80	<0.001	0.018	<0.02	<0.01	<2	0.094	0.012	0.13	8.32	<0.02	0.03	<0.001	<0.01	<0.01	0.01
646932	Drill Core	10.90	<2	<3	6	2.08	<0.001	0.022	<0.02	<0.01	<2	0.045	0.016	0.10	8.11	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646933	Drill Core	9.17	<2	<3	3	0.65	<0.001	0.010	<0.02	<0.01	<2	0.105	0.009	0.15	8.56	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646934	Drill Core	9.67	3	3	5	0.60	<0.001	0.009	<0.02	<0.01	<2	0.137	0.012	0.16	9.96	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646935	Drill Core	9.83	6	8	4	0.53	<0.001	0.010	<0.02	<0.01	<2	0.064	0.007	0.16	8.53	<0.02	0.04	<0.001	<0.01	<0.01	0.03
646936	Drill Core	9.16	<2	4	6	1.04	<0.001	0.019	<0.02	<0.01	<2	0.121	0.011	0.16	8.69	<0.02	0.02	<0.001	<0.01	<0.01	0.03
646937	Drill Core	9.23	<2	<3	6	1.51	<0.001	0.021	<0.02	<0.01	<2	0.104	0.012	0.17	9.37	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
646938	Drill Core	10.21	<2	<3	7	1.00	<0.001	0.018	<0.02	<0.01	<2	0.094	0.010	0.17	7.92	<0.02	<0.01	<0.001	<0.01	<0.01	0.04
646939	Drill Core	9.23	5	10	20	0.72	<0.001	0.024	<0.02	<0.01	<2	0.172	0.011	0.14	7.43	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
646940A	Drill Core	9.85	2	9	14	0.36	<0.001	0.015	<0.02	0.01	<2	0.185	0.011	0.16	8.58	<0.02	<0.01	<0.001	<0.01	<0.01	0.02



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 17, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000807.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
646911	Drill Core	0.06	<0.01	0.097	25.18	<0.01	0.06	<0.01	<0.01	<0.01	0.69	0.001	0.534	0.014	1.36	4.02	N.A.
646912	Drill Core	0.06	<0.01	0.082	24.58	<0.01	0.05	<0.01	<0.01	<0.01	0.82	0.029	0.632	0.013	0.96	2.07	2.92
646913	Drill Core	0.10	<0.01	0.154	23.32	<0.01	0.05	<0.01	<0.01	<0.01	0.90	0.041	0.630	0.020	1.15	2.83	N.A.
646914	Drill Core	3.56	0.04	0.048	18.80	0.13	2.15	<0.01	<0.01	<0.01	0.48	0.005	0.218	0.010	0.81	2.55	N.A.
646915	Drill Core	0.08	<0.01	0.169	23.69	<0.01	0.07	<0.01	<0.01	<0.01	0.62	0.001	0.236	0.013	0.94	4.17	N.A.
646916	Drill Core	0.95	<0.01	0.183	21.89	0.01	0.24	<0.01	<0.01	<0.01	0.72	0.010	0.204	0.011	0.80	3.70	N.A.
646917	Drill Core	0.17	<0.01	0.106	23.12	<0.01	0.04	<0.01	<0.01	<0.01	1.12	0.004	0.365	0.021	1.50	4.46	N.A.
646918	Drill Core	0.55	<0.01	0.096	23.87	<0.01	0.04	<0.01	<0.01	<0.01	1.19	0.021	0.380	0.018	1.52	3.67	N.A.
646919	Drill Core	0.19	<0.01	0.108	23.02	0.01	0.34	<0.01	<0.01	<0.01	0.96	0.001	0.250	0.021	1.40	3.57	N.A.
646920	Drill Core	1.81	0.02	0.002	0.32	0.07	6.46	3.43	1.12	<0.01	<0.01	0.008	0.002	<0.001	0.12	0.10	N.A.
646921	Drill Core	0.86	<0.01	0.115	22.48	0.03	0.45	<0.01	<0.01	<0.01	1.08	0.001	0.303	0.020	1.76	3.15	N.A.
646922	Drill Core	0.12	<0.01	0.049	23.47	0.02	0.44	<0.01	<0.01	<0.01	0.77	<0.001	0.254	0.015	1.40	3.90	N.A.
646923	Drill Core	0.06	<0.01	0.195	23.27	0.01	0.29	<0.01	<0.01	<0.01	0.74	<0.001	0.225	0.013	1.25	4.14	N.A.
646924	Drill Core	0.06	<0.01	0.127	22.95	<0.01	0.08	<0.01	<0.01	<0.01	0.89	<0.001	0.194	0.014	1.48	3.55	N.A.
646925	Rock Pulp	0.71	<0.01	0.145	23.13	0.02	0.31	<0.01	0.07	<0.01	1.11	0.001	0.250	0.013	1.39	3.81	N.A.
646926	Rock Pulp	4.30	<0.01	0.991	13.49	0.18	4.02	0.34	0.11	<0.01	0.45	0.036	0.198	0.007	0.61	0.60	N.A.
646927	Drill Core	0.48	<0.01	0.050	21.73	0.02	0.64	<0.01	<0.01	<0.01	1.64	0.005	0.118	0.021	2.34	2.95	N.A.
646928	Drill Core	0.08	<0.01	0.172	23.71	<0.01	0.08	<0.01	<0.01	<0.01	1.48	0.005	0.220	0.026	2.29	3.35	N.A.
646929	Drill Core	0.11	<0.01	0.302	24.61	<0.01	0.09	<0.01	<0.01	<0.01	1.56	0.009	0.394	0.018	1.70	3.38	N.A.
646930	Drill Core	1.26	<0.01	0.391	22.43	0.02	0.44	<0.01	0.05	<0.01	1.27	0.006	0.235	0.022	1.50	2.53	N.A.
646931	Drill Core	5.65	0.03	0.145	16.17	0.13	2.25	0.04	0.42	<0.01	0.71	0.005	0.094	0.010	1.30	1.19	N.A.
646932	Drill Core	7.69	<0.01	0.255	15.79	0.03	0.28	0.06	<0.01	<0.01	1.63	0.013	0.045	0.015	2.21	1.24	3.06
646933	Drill Core	4.01	<0.01	0.166	18.20	0.05	0.56	0.03	<0.01	<0.01	0.61	0.009	0.106	0.008	0.89	1.92	N.A.
646934	Drill Core	2.16	<0.01	0.139	18.92	0.03	0.43	0.01	<0.01	<0.01	0.57	0.009	0.141	0.011	0.78	1.73	N.A.
646935	Drill Core	4.15	0.07	0.115	11.38	0.30	4.52	1.70	0.79	<0.01	0.44	0.010	0.063	0.006	0.51	0.66	N.A.
646936	Drill Core	3.12	<0.01	0.168	16.10	0.09	1.15	0.27	0.32	<0.01	0.91	0.018	0.113	0.009	1.37	1.17	N.A.
646937	Drill Core	2.37	<0.01	0.129	16.35	0.05	0.32	0.13	0.07	<0.01	1.25	0.020	0.096	0.010	2.02	0.96	N.A.
646938	Drill Core	4.93	<0.01	0.149	15.45	0.06	0.33	0.21	0.06	<0.01	0.90	0.018	0.089	0.008	1.49	1.01	N.A.
646939	Drill Core	5.94	<0.01	0.171	17.00	0.05	0.30	0.04	<0.01	<0.01	0.65	0.011	0.177	0.009	1.14	1.10	N.A.
646940A	Drill Core	2.97	0.01	0.195	20.48	0.06	0.74	0.02	<0.01	<0.01	0.32	<0.001	0.161	0.008	1.03	2.67	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 17, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000807.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646940B	Client Dup	<2	12	14	0.35	<0.001	0.013	<0.02	0.01	<2	0.181	0.011	0.16	8.65	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	
646941	Drill Core	10.26	4	8	13	0.42	<0.001	0.008	<0.02	<0.01	<2	0.217	0.012	0.15	9.17	<0.02	<0.01	<0.001	<0.01	<0.01	
646942	Drill Core	10.02	2	7	9	0.37	<0.001	0.009	<0.02	<0.01	<2	0.187	0.011	0.15	8.40	<0.02	<0.01	<0.001	<0.01	<0.01	
646943	Drill Core	6.03	<2	35	23	6.68	0.005	0.096	<0.02	<0.01	<2	0.297	0.027	0.15	15.65	<0.02	<0.01	<0.001	<0.01	<0.01	
646944	Drill Core	3.78	<2	8	11	0.46	<0.001	0.027	<0.02	<0.01	<2	0.118	0.009	0.16	7.38	<0.02	0.06	<0.001	<0.01	<0.01	
646945	Drill Core	9.81	3	28	38	0.71	<0.001	0.051	<0.02	<0.01	<2	0.261	0.016	0.13	7.93	<0.02	<0.01	<0.001	<0.01	<0.01	
646946	Drill Core	11.84	4	23	30	0.79	<0.001	0.028	<0.02	<0.01	<2	0.278	0.017	0.10	7.93	<0.02	<0.01	<0.001	<0.01	<0.01	



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 17, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000807.1

Method		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
Unit		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
646940B	Client Dup	2.76	0.02	0.199	20.93	0.06	0.69	0.01	<0.01	<0.01	0.32	<0.001	0.156	0.007	1.12	3.01	N.A.
646941	Drill Core	1.62	<0.01	0.188	23.06	0.02	0.12	0.01	0.01	<0.01	0.36	<0.001	0.183	0.008	1.46	3.93	N.A.
646942	Drill Core	2.35	<0.01	0.189	21.55	0.03	0.15	0.02	<0.01	<0.01	0.31	0.001	0.171	0.008	1.15	3.04	N.A.
646943	Drill Core	5.80	<0.01	0.143	12.71	0.05	0.35	0.07	0.05	<0.01	4.77	0.098	0.265	0.025	1.17	0.32	N.A.
646944	Drill Core	4.50	0.10	0.131	10.81	0.24	5.50	1.02	2.14	<0.01	0.40	0.025	0.098	0.005	0.25	0.28	N.A.
646945	Drill Core	0.75	<0.01	0.184	23.82	0.02	0.14	<0.01	0.01	<0.01	0.62	0.047	0.222	0.012	0.70	2.55	N.A.
646946	Drill Core	0.24	<0.01	0.207	23.74	0.02	0.15	<0.01	0.01	<0.01	0.66	0.026	0.251	0.013	0.70	2.77	N.A.

QUALITY CONTROL REPORT

SMI08000807.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
Pulp Duplicates																					
646913	Drill Core	9.27	8	131	189	1.08	<0.001	0.048	<0.02	<0.01	<2	0.672	0.022	0.13	8.37	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646913	QC																				
646917	Drill Core	9.68	8	14	16	1.27	<0.001	0.030	<0.02	<0.01	<2	0.329	0.021	0.13	8.30	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646917	QC																				
646921	Drill Core	10.51	2	10	18	1.33	<0.001	0.029	<0.02	<0.01	<2	0.270	0.021	0.13	9.62	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646921	QC		3	12	17		<0.001	0.029	<0.02	<0.01	<2	0.273	0.021	0.13	9.75	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646931	Drill Core	9.65	<2	8	7	0.80	<0.001	0.018	<0.02	<0.01	<2	0.094	0.012	0.13	8.32	<0.02	0.03	<0.001	<0.01	<0.01	0.01
REP 646931	QC						<0.001	0.017	<0.02	<0.01	<2	0.092	0.012	0.13	8.26	<0.02	0.03	<0.001	<0.01	<0.01	0.01
646935	Drill Core	9.83	6	8	4	0.53	<0.001	0.010	<0.02	<0.01	<2	0.064	0.007	0.16	8.53	<0.02	0.04	<0.001	<0.01	<0.01	0.03
REP 646935	QC																				
646943	Drill Core	6.03	<2	35	23	6.68	0.005	0.096	<0.02	<0.01	<2	0.297	0.027	0.15	15.65	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
REP 646943	QC																				
646944	Drill Core	3.78	<2	8	11	0.46	<0.001	0.027	<0.02	<0.01	<2	0.118	0.009	0.16	7.38	<0.02	0.06	<0.001	<0.01	<0.01	0.01
REP 646944	QC																				
Core Reject Duplicates																					
646924	Drill Core	10.49	2	10	12	1.04	<0.001	0.029	<0.02	<0.01	<2	0.176	0.014	0.12	8.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
DUP 646924	QC		4	9	14	1.04	<0.001	0.033	<0.02	<0.01	<2	0.191	0.016	0.13	8.48	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
Reference Materials																					
STD CDN-PGMS-14	Standard		255	106	434																
STD CDN-PGMS-14	Standard		260	116	425																
STD CSC	Standard					4.32															
STD CSC	Standard					4.26															
STD FA10R	Standard		483	467	481																
STD FA10R	Standard		473	450	464																
STD OREAS76A	Standard					17.25															
STD OREAS76A	Standard					18.04															
STD R3NI	Standard																				
STD R3NI	Standard																				

QUALITY CONTROL REPORT

SMI08000807.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG	
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%		
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
Pulp Duplicates																	
646913	Drill Core	0.10	<0.01	0.154	23.32	<0.01	0.05	<0.01	<0.01	<0.01	0.90	0.041	0.630	0.020	1.15	2.83	N.A.
REP 646913	QC										0.041	0.623	0.020	1.16	2.86		
646917	Drill Core	0.17	<0.01	0.106	23.12	<0.01	0.04	<0.01	<0.01	<0.01	1.12	0.004	0.365	0.021	1.50	4.46	N.A.
REP 646917	QC										0.001	0.369	0.021	1.48	4.58		
646921	Drill Core	0.86	<0.01	0.115	22.48	0.03	0.45	<0.01	<0.01	<0.01	1.08	0.001	0.303	0.020	1.76	3.15	N.A.
REP 646921	QC	0.88	<0.01	0.116	22.75	0.03	0.46	<0.01	<0.01	<0.01	1.10						
646931	Drill Core	5.65	0.03	0.145	16.17	0.13	2.25	0.04	0.42	<0.01	0.71	0.005	0.094	0.010	1.30	1.19	N.A.
REP 646931	QC	5.68	0.03	0.126	16.29	0.13	2.22	0.04	0.42	<0.01	0.71						
646935	Drill Core	4.15	0.07	0.115	11.38	0.30	4.52	1.70	0.79	<0.01	0.44	0.010	0.063	0.006	0.51	0.66	N.A.
REP 646935	QC										0.010	0.063	0.006	0.52	0.67		
646943	Drill Core	5.80	<0.01	0.143	12.71	0.05	0.35	0.07	0.05	<0.01	4.77	0.098	0.265	0.025	1.17	0.32	N.A.
REP 646943	QC										0.110	0.303	0.028	4.25	0.59		
646944	Drill Core	4.50	0.10	0.131	10.81	0.24	5.50	1.02	2.14	<0.01	0.40	0.025	0.098	0.005	0.25	0.28	N.A.
REP 646944	QC										0.025	0.099	0.006	0.51	0.57		
Core Reject Duplicates																	
646924	Drill Core	0.06	<0.01	0.127	22.95	<0.01	0.08	<0.01	<0.01	<0.01	0.89	<0.001	0.194	0.014	1.48	3.55	N.A.
DUP 646924	QC	0.10	<0.01	0.133	24.73	<0.01	0.08	<0.01	<0.01	<0.01	1.01	0.003	0.198	0.014	1.57	3.57	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																
STD OREAS76A	Standard																
STD R3NI	Standard										0.635	0.400	0.052	3.89	0.15		
STD R3NI	Standard										0.751	0.354	0.048	2.94	0.10		

QUALITY CONTROL REPORT

SMI08000807.1

		WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
STD SF-3A_NI	Standard																				
STD SF-3T	Standard					0.032	0.775	0.93	1.09	52	0.347	0.018	0.42	8.13	<0.02	0.04	0.005	<0.01	<0.01	0.01	
STD SF-3T	Standard					0.032	0.780	0.94	1.10	53	0.348	0.018	0.43	8.15	<0.02	0.04	0.005	<0.01	<0.01	0.01	
STD SF-3T	Standard					0.032	0.754	0.93	1.08	53	0.344	0.018	0.43	8.06	<0.02	0.04	0.004	<0.01	<0.01	0.01	
STD SF-3T	Standard					0.032	0.766	0.93	1.09	53	0.350	0.018	0.42	8.09	<0.02	0.04	0.005	<0.01	<0.01	0.01	
STD SF-3T Expected						0.032	0.7723	0.961	1.0672	52	0.35	0.0181	0.432	8.33	0.004	0.044	0.00475	0.00111	0.00048	0.0143	
STD FA10R Expected			485	472	476																
STD CDN-PGMS-14			259	119	451																
STD CSC Expected						4.25															
STD OREAS76A Expected						18															
STD R3NI Expected																					
STD SF-3A_NI Expected																					
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank																				
BLK	Blank					<0.02															
BLK	Blank					<0.02															
BLK	Blank																				
BLK	Blank																				
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.001	<0.001	0.08	2.49	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank	<0.01	<2	<3	<2	0.03	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.08	2.52	<0.02	0.07	<0.001	<0.01	<0.01	<0.01

QUALITY CONTROL REPORT

SMI08000807.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
STD SF-3A_NI	Standard											0.792	0.310	0.015	1.56	2.09	
STD SF-3T	Standard	4.04	0.05	0.020	4.53	0.20	5.39	2.05	2.45	<0.01	3.79						
STD SF-3T	Standard	4.03	0.06	0.020	4.56	0.20	5.43	2.04	2.48	<0.01	3.92						
STD SF-3T	Standard	3.99	0.05	0.020	4.52	0.19	5.34	2.03	2.44	<0.01	3.93						
STD SF-3T	Standard	4.03	0.05	0.020	4.55	0.20	5.37	2.07	2.45	<0.01	3.96						
STD SF-3T Expected		4.1	0.06	0.02074	4.67	0.19	5.43	2.06	2.47	0.00043	3.5						
STD FA10R Expected																	
STD CDN-PGMS-14																	
STD CSC Expected																	
STD OREAS76A Expected																	
STD R3NI Expected													0.42				
STD SF-3A_NI Expected													0.3205				
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank																
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
Prep Wash																	
G1	Prep Blank	2.51	0.07	<0.001	0.64	0.25	6.78	2.63	2.88	<0.01	<0.01	<0.001	<0.001	<0.001	0.14	0.06	N.A.
G1	Prep Blank	2.52	0.08	0.001	0.64	0.24	6.96	2.59	2.92	<0.01	<0.01	<0.001	<0.001	<0.001	0.13	0.06	N.A.

Hole 08-260

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Email Distribution List
 Receiving Lab: Canada-Smithers
 Received: September 08, 2008
 Report Date: October 30, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000883.1

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-260A
 P.O. Number
 Number of Samples: 48

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC: Email Distribution List

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	44	Crush split and pulverize drill core to 200 mesh		
3B	48	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	48	Analysis by Leco	0.1	Completed
7TD	48	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	48	Leached with H2O2 + NH4 citrate	1	Completed
Specific Gravity	4	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.
 All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.
 "**" asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

ACME ANALYTICAL LABORATORIES LTD.

www.acmelab.com

Client:

Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project:

Turnagain

Report Date:

October 30, 2008

Page:

2 of 3

Part 1

CERTIFICATE OF ANALYSIS

SMI08000883.1

Method	WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646947	Drill Core	7.82	<2	<3	5	0.21	<0.001	0.009	<0.02	<0.01	<2	0.111	0.010	0.13	6.67	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646948	Drill Core	9.23	<2	13	27	0.27	<0.001	0.018	<0.02	<0.01	<2	0.253	0.011	0.12	6.78	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646949	Drill Core	10.78	<2	32	36	0.25	<0.001	0.018	<0.02	<0.01	<2	0.275	0.012	0.13	7.15	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646950	Rock Pulp	0.02	I.S.	I.S.	I.S.	0.36	<0.001	0.052	<0.02	0.02	<2	0.227	0.011	0.10	8.66	<0.02	<0.01	<0.001	0.01	<0.01	0.02
646951	Rock Pulp	0.02	I.S.	I.S.	I.S.	1.25	<0.001	0.028	<0.02	<0.01	<2	0.237	0.015	0.11	8.05	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646952	Drill Core	9.24	3	35	40	0.43	<0.001	0.020	<0.02	<0.01	<2	0.264	0.013	0.11	7.70	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646953	Drill Core	9.67	<2	17	23	0.46	<0.001	0.016	<0.02	<0.01	<2	0.224	0.015	0.14	8.35	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646954	Drill Core	9.17	<2	3	9	0.19	<0.001	0.005	<0.02	<0.01	<2	0.203	0.011	0.10	5.61	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646955	Drill Core	9.05	<2	7	22	0.28	<0.001	0.011	<0.02	<0.01	<2	0.263	0.011	0.10	5.35	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646956	Drill Core	9.19	6	15	17	0.16	<0.001	0.005	<0.02	<0.01	<2	0.265	0.009	0.09	4.79	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646957	Drill Core	9.16	<2	10	11	0.15	<0.001	0.004	<0.02	<0.01	<2	0.275	0.010	0.11	4.99	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646958	Drill Core	8.45	<2	<3	11	0.37	<0.001	0.011	<0.02	<0.01	<2	0.194	0.011	0.11	6.39	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646959	Drill Core	10.25	6	84	135	5.08	<0.001	0.109	<0.02	<0.01	<2	0.560	0.029	0.13	13.68	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646960	Drill Core	9.38	19	186	75	5.67	<0.001	0.116	<0.02	<0.01	<2	0.474	0.032	0.11	14.43	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646961	Drill Core	9.36	3	58	34	2.99	0.001	0.067	<0.02	<0.01	<2	0.328	0.019	0.10	9.70	<0.02	0.01	<0.001	<0.01	<0.01	0.03
646962	Drill Core	9.47	4	<3	18	2.56	0.002	0.042	<0.02	<0.01	<2	0.228	0.018	0.12	9.16	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646963	Drill Core	9.49	6	5	37	5.02	<0.001	0.071	<0.02	0.01	<2	0.347	0.032	0.12	14.00	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646964	Drill Core	9.26	<2	<3	5	0.80	<0.001	0.012	<0.02	<0.01	<2	0.150	0.012	0.12	7.58	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646965	Drill Core	9.18	<2	10	9	1.60	<0.001	0.029	<0.02	0.01	<2	0.204	0.019	0.13	8.75	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646966	Drill Core	9.29	<2	9	12	1.96	<0.001	0.032	<0.02	<0.01	<2	0.268	0.022	0.13	10.09	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646967	Drill Core	9.46	<2	4	8	0.85	<0.001	0.018	<0.02	<0.01	<2	0.223	0.015	0.11	7.84	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646968	Drill Core	9.12	7	<3	7	0.34	<0.001	0.007	<0.02	<0.01	<2	0.190	0.012	0.11	6.94	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646969	Drill Core	10.80	<2	<3	<2	0.40	<0.001	0.009	<0.02	<0.01	<2	0.171	0.013	0.11	7.42	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646970A	Drill Core	9.97	<2	22	10	1.72	<0.001	0.058	<0.02	<0.01	<2	0.227	0.020	0.12	9.76	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646970B	Client Dup		<2	7	12	1.82	<0.001	0.054	<0.02	<0.01	<2	0.231	0.020	0.11	9.50	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646971	Drill Core	10.18	<2	7	22	2.50	<0.001	0.078	<0.02	<0.01	<2	0.287	0.022	0.12	10.06	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646972	Drill Core	9.69	4	15	45	3.29	<0.001	0.094	<0.02	<0.01	<2	0.489	0.034	0.12	12.23	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646973	Drill Core	9.24	<2	7	15	0.41	<0.001	0.017	<0.02	<0.01	<2	0.238	0.012	0.11	6.70	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646974	Drill Core	9.82	<2	17	31	3.54	0.002	0.053	<0.02	<0.01	<2	0.237	0.018	0.10	11.91	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646975	Rock Pulp	0.02	I.S.	I.S.	I.S.	4.16	<0.001	0.043	<0.02	<0.01	<2	0.365	0.025	0.11	11.43	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 30, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000883.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
646947	Drill Core	5.08	<0.01	0.142	18.63	0.09	0.69	0.04	0.07	<0.01	0.28	<0.001	0.084	0.007	0.94	2.74	N.A.
646948	Drill Core	2.61	<0.01	0.114	21.10	0.06	0.41	0.03	0.07	<0.01	0.34	0.001	0.207	0.009	0.75	2.47	N.A.
646949	Drill Core	1.69	<0.01	0.141	23.05	0.05	0.36	0.01	0.09	<0.01	0.37	0.009	0.212	0.009	1.07	3.35	N.A.
646950	Rock Pulp	4.08	<0.01	1.037	12.73	0.17	3.93	0.32	0.11	<0.01	0.46	0.033	0.188	0.007	0.65	0.64	N.A.
646951	Rock Pulp	0.64	<0.01	0.136	21.67	0.02	0.29	<0.01	0.07	<0.01	1.16	0.002	0.226	0.013	1.41	4.19	N.A.
646952	Drill Core	1.50	<0.01	0.145	20.88	0.07	0.58	0.03	0.12	<0.01	0.53	0.001	0.235	0.012	0.82	2.55	2.86
646953	Drill Core	2.08	<0.01	0.162	21.54	0.09	0.53	0.01	0.03	<0.01	0.71	0.001	0.188	0.012	0.88	2.10	N.A.
646954	Drill Core	0.96	<0.01	0.121	21.49	0.07	0.66	<0.01	0.08	<0.01	0.25	<0.001	0.186	0.009	0.60	2.94	N.A.
646955	Drill Core	2.03	0.01	0.066	20.07	0.12	1.43	0.01	0.07	<0.01	0.38	<0.001	0.242	0.010	0.59	2.29	N.A.
646956	Drill Core	1.40	<0.01	0.065	20.71	0.11	0.82	<0.01	0.12	<0.01	0.25	0.002	0.257	0.009	0.51	2.39	N.A.
646957	Drill Core	0.23	<0.01	0.091	23.77	0.08	0.61	<0.01	0.09	<0.01	0.25	<0.001	0.232	0.008	0.72	3.65	N.A.
646958	Drill Core	1.05	<0.01	0.119	21.40	0.07	0.50	<0.01	0.06	<0.01	0.49	<0.001	0.175	0.010	0.90	2.89	N.A.
646959	Drill Core	1.53	<0.01	0.120	18.07	0.05	0.37	<0.01	0.04	<0.01	3.94	0.033	0.566	0.028	3.75	1.95	N.A.
646960	Drill Core	1.03	<0.01	0.106	17.90	0.05	0.34	<0.01	0.04	<0.01	4.47	0.023	0.485	0.032	3.84	1.40	N.A.
646961	Drill Core	2.81	0.02	0.090	13.25	0.12	1.75	0.68	0.85	<0.01	2.36	0.033	0.323	0.018	2.22	0.50	N.A.
646962	Drill Core	2.23	<0.01	0.125	17.83	0.07	0.55	0.11	0.28	<0.01	2.48	0.040	0.228	0.015	0.63	0.37	N.A.
646963	Drill Core	3.69	<0.01	0.135	16.03	0.05	0.34	0.02	<0.01	<0.01	4.15	0.064	0.361	0.029	1.01	0.58	N.A.
646964	Drill Core	2.14	<0.01	0.182	22.03	0.06	0.39	0.02	0.05	<0.01	0.75	0.011	0.135	0.010	0.31	0.86	N.A.
646965	Drill Core	1.04	<0.01	0.181	22.84	0.03	0.27	0.01	0.05	<0.01	1.35	0.024	0.194	0.015	0.52	0.99	N.A.
646966	Drill Core	0.41	<0.01	0.251	23.61	0.03	0.24	<0.01	0.05	<0.01	1.71	0.026	0.260	0.017	0.62	1.18	N.A.
646967	Drill Core	0.79	<0.01	0.170	23.16	0.04	0.28	<0.01	0.05	<0.01	0.79	0.015	0.203	0.011	0.45	0.99	N.A.
646968	Drill Core	1.50	<0.01	0.150	23.60	0.04	0.24	0.01	0.03	<0.01	0.32	0.006	0.143	0.007	0.38	1.18	N.A.
646969	Drill Core	2.42	<0.01	0.162	23.03	0.04	0.24	0.02	0.02	<0.01	0.39	0.009	0.121	0.006	0.39	1.02	N.A.
646970A	Drill Core	1.82	<0.01	0.186	22.04	0.03	0.25	0.01	<0.01	<0.01	1.46	0.057	0.206	0.014	0.63	1.02	N.A.
646970B	Client Dup	1.69	<0.01	0.172	21.35	0.03	0.25	0.01	<0.01	<0.01	1.66	0.051	0.208	0.014	0.67	1.13	N.A.
646971	Drill Core	0.84	0.01	0.202	21.93	0.05	0.35	0.01	0.05	<0.01	2.10	0.074	0.274	0.018	0.82	1.09	N.A.
646972	Drill Core	0.63	<0.01	0.207	20.66	0.04	0.33	<0.01	<0.01	<0.01	2.88	0.086	0.483	0.030	1.09	1.36	2.89
646973	Drill Core	0.44	<0.01	0.122	23.10	0.04	0.25	<0.01	<0.01	<0.01	0.38	0.013	0.184	0.008	0.36	0.96	N.A.
646974	Drill Core	3.04	<0.01	0.117	17.02	0.06	0.38	0.01	<0.01	<0.01	2.79	0.052	0.226	0.016	0.64	0.66	N.A.
646975	Rock Pulp	1.04	0.01	0.160	18.40	0.02	0.26	0.05	0.09	<0.01	3.10	0.045	0.392	0.023	1.13	1.58	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 30, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000883.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01		
646976	Rock Pulp	0.02	I.S.	I.S.	I.S.	0.48	<0.001	0.054	<0.02	0.02	<2	0.231	0.011	0.10	8.67	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646977	Drill Core	9.29	3	10	18	2.19	0.001	0.045	<0.02	0.01	<2	0.172	0.013	0.10	9.26	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646978	Drill Core	9.84	4	<3	7	1.31	<0.001	0.066	<0.02	<0.01	<2	0.203	0.013	0.13	8.14	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646979	Drill Core	9.92	3	10	23	4.19	0.003	0.126	<0.02	<0.01	<2	0.192	0.025	0.12	11.56	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
646980	Drill Core	1.76	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	1.09	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
646981	Drill Core	10.64	4	9	24	2.15	<0.001	0.090	<0.02	<0.01	<2	0.220	0.023	0.13	10.15	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646982	Drill Core	10.55	6	11	21	1.19	<0.001	0.073	<0.02	<0.01	<2	0.206	0.021	0.14	10.07	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646983	Drill Core	11.02	5	24	25	0.53	<0.001	0.053	<0.02	<0.01	<2	0.163	0.017	0.14	8.80	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646984	Drill Core	10.87	12	71	89	0.45	<0.001	0.080	<0.02	<0.01	<2	0.201	0.014	0.14	8.45	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646985	Drill Core	8.86	22	24	25	1.48	<0.001	0.149	<0.02	<0.01	2	0.352	0.019	0.12	9.22	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646986	Drill Core	9.34	18	41	37	0.81	<0.001	0.136	<0.02	<0.01	<2	0.277	0.014	0.14	8.95	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646987	Drill Core	9.29	7	45	69	0.57	<0.001	0.071	<0.02	<0.01	<2	0.188	0.014	0.14	8.36	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646988	Drill Core	10.42	5	28	14	0.51	<0.001	0.022	<0.02	<0.01	<2	0.127	0.012	0.14	7.83	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646989	Drill Core	9.45	6	61	86	1.05	<0.001	0.038	<0.02	<0.01	<2	0.196	0.015	0.15	9.44	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646990	Drill Core	11.45	4	7	12	3.32	<0.001	0.104	<0.02	<0.01	<2	0.242	0.023	0.12	10.75	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
646991	Drill Core	10.36	7	42	27	6.11	<0.001	0.189	<0.02	<0.01	<2	0.500	0.041	0.13	16.87	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646992	Drill Core	10.71	4	13	15	1.56	<0.001	0.059	<0.02	0.01	<2	0.266	0.019	0.16	10.51	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646993	Drill Core	10.26	10	19	28	2.98	<0.001	0.124	<0.02	<0.01	<2	0.368	0.025	0.13	13.42	<0.02	<0.01	<0.001	<0.01	<0.01	0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 30, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000883.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
646976	Rock Pulp	4.20	0.01	0.986	13.01	0.17	3.87	0.29	0.12	<0.01	0.51	0.055	0.182	0.007	0.32	0.27	N.A.
646977	Drill Core	3.08	<0.01	0.171	17.65	0.06	0.44	0.02	0.01	<0.01	1.74	0.042	0.157	0.011	0.42	0.58	N.A.
646978	Drill Core	1.97	<0.01	0.161	22.38	0.04	0.40	0.01	0.02	<0.01	1.22	0.069	0.188	0.010	0.60	1.30	N.A.
646979	Drill Core	7.94	0.02	0.110	13.53	0.07	0.43	0.05	<0.01	<0.01	3.34	0.123	0.184	0.021	1.02	0.57	N.A.
646980	Drill Core	1.89	0.03	<0.001	0.20	0.07	6.87	3.26	1.15	<0.01	0.02	<0.001	<0.001	<0.001	0.06	0.02	N.A.
646981	Drill Core	1.98	0.02	0.108	20.97	0.03	0.30	0.02	<0.01	<0.01	1.76	0.088	0.216	0.019	0.85	1.35	N.A.
646982	Drill Core	1.34	0.01	0.156	23.01	0.02	0.15	0.01	<0.01	<0.01	1.09	0.070	0.164	0.013	0.69	1.43	3.28
646983	Drill Core	2.31	0.01	0.121	23.33	0.03	0.18	0.02	<0.01	<0.01	0.50	0.048	0.105	0.007	0.43	0.94	N.A.
646984	Drill Core	1.59	0.01	0.126	23.31	0.02	0.16	0.01	<0.01	<0.01	0.43	0.079	0.146	0.008	0.91	2.70	N.A.
646985	Drill Core	1.69	0.02	0.102	19.65	0.03	0.22	<0.01	<0.01	<0.01	1.19	0.155	0.345	0.016	0.90	1.30	N.A.
646986	Drill Core	2.79	0.02	0.116	20.94	0.07	0.36	0.02	0.03	<0.01	0.74	0.129	0.233	0.009	0.66	1.00	N.A.
646987	Drill Core	2.23	0.02	0.120	21.75	0.04	0.22	0.01	0.02	<0.01	0.54	0.064	0.141	0.008	0.61	1.40	N.A.
646988	Drill Core	2.29	0.03	0.115	20.39	0.02	0.16	0.01	<0.01	<0.01	0.46	0.021	0.099	0.007	0.42	1.17	N.A.
646989	Drill Core	1.48	0.03	0.135	22.09	0.02	0.17	<0.01	<0.01	<0.01	0.98	0.032	0.163	0.011	0.46	0.92	N.A.
646990	Drill Core	6.05	0.02	0.118	16.16	0.05	0.31	0.03	<0.01	<0.01	2.70	0.101	0.237	0.020	0.73	0.70	N.A.
646991	Drill Core	1.71	0.03	0.137	18.53	0.02	0.16	0.01	<0.01	<0.01	4.66	0.181	0.489	0.036	1.55	0.99	N.A.
646992	Drill Core	3.08	0.02	0.162	20.55	0.03	0.19	0.02	<0.01	<0.01	1.39	0.055	0.228	0.013	0.63	0.96	3.28
646993	Drill Core	1.86	0.03	0.146	19.60	0.02	0.15	0.01	<0.01	<0.01	2.42	0.119	0.387	0.023	1.04	1.05	N.A.

QUALITY CONTROL REPORT

SMI08000883.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
Pulp Duplicates																					
646948	Drill Core	9.23	<2	13	27	0.27	<0.001	0.018	<0.02	<0.01	<2	0.253	0.011	0.12	6.78	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646948	QC																				
REP 646959	QC	4.32																			
646965	Drill Core	9.18	<2	10	9	1.60	<0.001	0.029	<0.02	0.01	<2	0.204	0.019	0.13	8.75	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646965	QC																				
646968	Drill Core	9.12	7	<3	7	0.34	<0.001	0.007	<0.02	<0.01	<2	0.190	0.012	0.11	6.94	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646968	QC	0.33																			
646970A	Drill Core	9.97	<2	22	10	1.72	<0.001	0.058	<0.02	<0.01	<2	0.227	0.020	0.12	9.76	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646970A	QC	<0.001 0.057 <0.02 <0.01 <2 0.220 0.019 0.11 9.44 <0.02 <0.01 <0.001 <0.01 <0.01 <0.01																			
646974	Drill Core	9.82	<2	17	31	3.54	0.002	0.053	<0.02	<0.01	<2	0.237	0.018	0.10	11.91	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
REP 646974	QC	<2 12 32																			
646985	Drill Core	8.86	22	24	25	1.48	<0.001	0.149	<0.02	<0.01	2	0.352	0.019	0.12	9.22	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646985	QC																				
646988	Drill Core	10.42	5	28	14	0.51	<0.001	0.022	<0.02	<0.01	<2	0.127	0.012	0.14	7.83	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 646988	QC	<2 21 15																			
Core Reject Duplicates																					
646959	Drill Core	10.25	6	84	135	5.08	<0.001	0.109	<0.02	<0.01	<2	0.560	0.029	0.13	13.68	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
DUP 646959	QC	7 55 136 4.37 <0.001 0.102 <0.02 <0.01 <2 0.494 0.025 0.13 12.48 <0.02 <0.01 <0.001 <0.01 <0.01 <0.01																			
646993	Drill Core	10.26	10	19	28	2.98	<0.001	0.124	<0.02	<0.01	<2	0.368	0.025	0.13	13.42	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
DUP 646993	QC	11 25 28 2.91 <0.001 0.119 <0.02 <0.01 <2 0.365 0.024 0.13 13.00 <0.02 <0.01 <0.001 <0.01 <0.01 <0.01																			
Reference Materials																					
STD CDN-PGMS-14	Standard	269 115 423																			
STD CSC	Standard	4.03																			
STD CSC	Standard	4.19																			
STD FA10R	Standard	493 489 512																			
STD FA10R	Standard	450 446 464																			
STD FA10R	Standard	466 460 481																			
STD FA10R	Standard	476 445 486																			

QUALITY CONTROL REPORT

SMI08000883.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG	
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%		
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
Pulp Duplicates																	
646948	Drill Core	2.61	<0.01	0.114	21.10	0.06	0.41	0.03	0.07	<0.01	0.34	0.001	0.207	0.009	0.75	2.47	N.A.
REP 646948	QC											0.009	0.206	0.009	0.78	2.46	
REP 646959	QC																
646965	Drill Core	1.04	<0.01	0.181	22.84	0.03	0.27	0.01	0.05	<0.01	1.35	0.024	0.194	0.015	0.52	0.99	N.A.
REP 646965	QC											0.024	0.191	0.015	0.51	0.95	
646968	Drill Core	1.50	<0.01	0.150	23.60	0.04	0.24	0.01	0.03	<0.01	0.32	0.006	0.143	0.007	0.38	1.18	N.A.
REP 646968	QC																
646970A	Drill Core	1.82	<0.01	0.186	22.04	0.03	0.25	0.01	<0.01	<0.01	1.46	0.057	0.206	0.014	0.63	1.02	N.A.
REP 646970A	QC	1.76	<0.01	0.183	21.44	0.03	0.25	0.01	0.01	<0.01	1.41						
646974	Drill Core	3.04	<0.01	0.117	17.02	0.06	0.38	0.01	<0.01	<0.01	2.79	0.052	0.226	0.016	0.64	0.66	N.A.
REP 646974	QC																
646985	Drill Core	1.69	0.02	0.102	19.65	0.03	0.22	<0.01	<0.01	<0.01	1.19	0.155	0.345	0.016	0.90	1.30	N.A.
REP 646985	QC											0.157	0.348	0.016	0.84	1.01	
646988	Drill Core	2.29	0.03	0.115	20.39	0.02	0.16	0.01	<0.01	<0.01	0.46	0.021	0.099	0.007	0.42	1.17	N.A.
REP 646988	QC																
Core Reject Duplicates																	
646959	Drill Core	1.53	<0.01	0.120	18.07	0.05	0.37	<0.01	0.04	<0.01	3.94	0.033	0.566	0.028	3.75	1.95	N.A.
DUP 646959	QC	1.50	<0.01	0.112	18.64	0.05	0.37	<0.01	0.04	<0.01	3.63	0.019	0.504	0.025	3.92	1.69	N.A.
646993	Drill Core	1.86	0.03	0.146	19.60	0.02	0.15	0.01	<0.01	<0.01	2.42	0.119	0.387	0.023	1.04	1.05	N.A.
DUP 646993	QC	1.82	0.02	0.145	20.02	0.02	0.15	0.01	<0.01	<0.01	2.36	0.102	0.326	0.019	0.87	0.90	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CSC	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																

QUALITY CONTROL REPORT

SMI08000883.1

	WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
STD FA10R	Standard	436	443	443																
STD OREAS76A	Standard				17.80															
STD OREAS76A	Standard				17.81															
STD R4T	Standard					0.060	0.495	1.51	3.30	85	0.347	0.039	0.09	23.92	<0.02	0.02	0.017	0.01	<0.01	0.02
STD R4T	Standard					0.061	0.504	1.55	3.41	89	0.354	0.041	0.09	23.78	<0.02	0.02	0.019	0.01	<0.01	0.02
STD R4T	Standard					0.063	0.512	1.56	3.52	91	0.350	0.039	0.09	24.68	<0.02	0.02	0.018	0.02	<0.01	0.02
STD SF-3A_NI	Standard																			
STD SF-3A_NI	Standard																			
STD SF-3T	Standard					0.030	0.757	0.92	1.05	51	0.339	0.016	0.42	8.20	<0.02	0.04	0.004	<0.01	<0.01	0.01
STD SF-3T	Standard					0.031	0.765	0.94	1.05	53	0.350	0.018	0.43	8.31	<0.02	0.04	0.005	<0.01	<0.01	0.01
STD SF-3T	Standard					0.032	0.770	0.95	1.09	53	0.346	0.018	0.42	8.02	<0.02	0.04	0.004	<0.01	<0.01	0.01
STD CDN-PGMS-14		259	119	451																
STD FA10R Expected		485	472	476																
STD SF-3T Expected						0.032	0.7723	0.961	1.0672	52	0.35	0.0181	0.432	8.33	0.004	0.044	0.00475	0.00111	0.00048	0.0143
STD R4T Expected						0.062	0.502	1.518	3.376	86	0.348	0.039	0.086	24.07	0.0087	0.0185	0.018	0.0138	0.0018	0.016
STD CSC Expected					4.25															
STD OREAS76A Expected					18															
STD SF-3A_NI Expected																				
BLK	Blank	<2	<3	<2																
BLK	Blank	<2	<3	<2																
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
BLK	Blank	<2	<3	<2																
BLK	Blank	<2	<3	<2																
BLK	Blank	<2	<3	<2																
BLK	Blank	<2	<3	<2																
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
BLK	Blank				<0.02															
BLK	Blank																			

QUALITY CONTROL REPORT

SMI08000883.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
STD FA10R	Standard																
STD OREAS76A	Standard																
STD OREAS76A	Standard																
STD R4T	Standard	2.13	0.04	0.019	1.39	0.18	3.89	0.89	1.15	<0.01	12.11						
STD R4T	Standard	2.19	0.04	0.019	1.41	0.19	3.88	1.29	1.17	<0.01	12.31						
STD R4T	Standard	2.13	0.04	0.018	1.42	0.20	3.93	0.90	1.15	<0.01	13.44						
STD SF-3A_NI	Standard											0.760	0.314	0.014	1.62	1.87	
STD SF-3A_NI	Standard											0.042	0.344	0.017	3.60	3.55	
STD SF-3T	Standard	3.96	0.05	0.020	4.48	0.18	5.34	2.03	2.38	<0.01	4.13						
STD SF-3T	Standard	4.11	0.04	0.015	4.63	0.19	5.38	1.96	1.98	<0.01	4.28						
STD SF-3T	Standard	4.01	0.05	0.020	4.56	0.20	5.49	2.08	2.44	<0.01	4.29						
STD CDN-PGMS-14																	
STD FA10R Expected																	
STD SF-3T Expected		4.1	0.06	0.02074	4.67	0.19	5.43	2.06	2.47	0.00043	3.5						
STD R4T Expected		2.166	0.045	0.018	1.384		3.897	0.9	1.153	0.00016							
STD CSC Expected																	
STD OREAS76A Expected																	
STD SF-3A_NI Expected												0.3205					
BLK	Blank																
BLK	Blank																
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	

QUALITY CONTROL REPORT

SMI08000883.1

		WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
BLK	Blank	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
BLK	Blank	<0.02																			
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.42	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank	<0.01	4	<3	<2	0.03	<0.001	<0.001	<0.02	<0.01	<2	0.002	<0.001	0.07	2.50	<0.02	0.07	<0.001	<0.01	<0.01	<0.01

QUALITY CONTROL REPORT

SMI08000883.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
Prep Wash																	
G1	Prep Blank	2.48	0.08	<0.001	0.72	0.23	7.84	2.63	1.74	<0.01	0.01	<0.001	<0.001	<0.001	0.13	0.06	N.A.
G1	Prep Blank	2.49	0.08	0.002	0.79	0.23	7.80	2.57	1.98	<0.01	0.05	<0.001	<0.001	<0.001	0.23	0.10	N.A.

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Email Distribution List
 Receiving Lab: Canada-Smithers
 Received: September 08, 2008
 Report Date: November 06, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000879.1

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-260B
 P.O. Number
 Number of Samples: 48

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	44	Crush split and pulverize drill core to 200 mesh		
3B	48	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	48	Analysis by Leco	0.1	Completed
7TD	48	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	48	Leached with H2O2 + NH4 citrate	1	Completed
Specific Gravity	2	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. ** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

ACME ANALYTICAL LABORATORIES LTD.

www.acmelab.com

Client:

Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project:

Turnagain

Report Date:

November 06, 2008

Page:

2 of 3

Part 1

CERTIFICATE OF ANALYSIS

SMI08000879.1

Method	WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
646994	Drill Core	10.26	3	42	29	2.45	<0.001	0.054	<0.02	<0.01	<2	0.256	0.017	0.14	11.00	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646995	Drill Core	8.73	<2	12	12	0.85	<0.001	0.049	<0.02	<0.01	<2	0.161	0.013	0.14	9.21	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646996	Drill Core	7.37	8	36	48	0.80	<0.001	0.081	<0.02	<0.01	<2	0.198	0.015	0.13	9.12	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
646997	Drill Core	9.22	4	19	13	0.56	<0.001	0.020	<0.02	<0.01	<2	0.118	0.009	0.13	7.24	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
646998	Drill Core	9.47	2	23	15	0.55	<0.001	0.023	<0.02	<0.01	<2	0.128	0.010	0.14	7.50	<0.02	0.02	<0.001	<0.01	<0.01	<0.01
646999	Drill Core	9.42	<2	21	13	0.76	<0.001	0.028	<0.02	<0.01	<2	0.134	0.011	0.12	8.72	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647000	Rock Pulp	0.02	I.S.	I.S.	I.S.	1.28	<0.001	0.029	<0.02	<0.01	<2	0.258	0.016	0.12	9.03	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647001	Rock Pulp	0.02	I.S.	I.S.	I.S.	0.47	<0.001	0.048	<0.02	0.02	<2	0.218	0.010	0.10	8.32	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
647002	Drill Core	10.63	2	6	6	0.92	<0.001	0.042	<0.02	<0.01	<2	0.148	0.015	0.13	9.34	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647003	Drill Core	10.47	<2	56	70	0.68	<0.001	0.043	<0.02	<0.01	<2	0.236	0.015	0.12	8.07	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647004	Drill Core	9.72	<2	11	13	0.13	<0.001	0.002	<0.02	<0.01	<2	0.192	0.011	0.10	5.95	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647005	Drill Core	9.51	<2	10	6	0.04	<0.001	<0.001	<0.02	<0.01	<2	0.215	0.011	0.11	6.49	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647006	Drill Core	10.55	7	14	9	0.07	<0.001	<0.001	<0.02	<0.01	<2	0.186	0.011	0.11	6.24	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647007	Drill Core	9.35	<2	8	14	0.10	<0.001	0.008	<0.02	<0.01	<2	0.061	0.005	0.13	5.62	<0.02	0.05	<0.001	<0.01	<0.01	0.01
647008	Drill Core	9.43	<2	18	24	0.09	<0.001	0.005	<0.02	<0.01	<2	0.222	0.012	0.10	6.34	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647009	Drill Core	9.49	<2	31	35	0.11	<0.001	0.011	<0.02	<0.01	<2	0.237	0.011	0.09	5.96	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647010	Drill Core	2.17	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.06	1.02	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
647011	Drill Core	8.82	10	10	3	0.21	<0.001	0.007	<0.02	<0.01	<2	0.205	0.010	0.10	6.02	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647012	Drill Core	9.05	3	15	12	0.27	<0.001	0.008	<0.02	<0.01	<2	0.209	0.009	0.14	7.30	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
647013	Drill Core	8.93	5	17	12	0.26	<0.001	0.007	<0.02	<0.01	<2	0.214	0.010	0.12	6.82	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647014	Drill Core	8.74	2	13	8	0.55	<0.001	0.009	<0.02	<0.01	<2	0.185	0.010	0.12	7.10	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
647015	Drill Core	8.85	<2	15	8	0.45	<0.001	0.009	<0.02	<0.01	<2	0.137	0.009	0.15	6.59	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
647016	Drill Core	9.89	3	28	22	0.97	<0.001	0.031	<0.02	<0.01	<2	0.252	0.014	0.12	7.86	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
647017	Drill Core	7.51	<2	22	13	0.33	<0.001	0.013	<0.02	<0.01	<2	0.199	0.010	0.12	6.33	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
647018	Drill Core	7.72	<2	13	2	0.33	<0.001	0.006	<0.02	<0.01	<2	0.148	0.009	0.15	7.51	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
647019	Drill Core	10.36	<2	10	8	0.93	<0.001	0.012	<0.02	<0.01	<2	0.191	0.012	0.13	7.84	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647020	Drill Core	10.73	<2	6	9	1.72	<0.001	0.028	<0.02	<0.01	<2	0.206	0.017	0.12	9.25	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
647021	Drill Core	10.08	3	10	13	1.06	<0.001	0.017	<0.02	<0.01	<2	0.235	0.014	0.12	8.84	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647022	Drill Core	9.81	<2	13	9	1.04	<0.001	0.017	<0.02	<0.01	<2	0.189	0.012	0.12	8.62	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647023	Drill Core	10.78	<2	16	13	2.53	<0.001	0.028	<0.02	<0.01	<2	0.278	0.024	0.13	11.06	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: November 06, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000879.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S		Cu	Ni	Co	Fe	Mg	SG
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
646994	Drill Core	3.13	0.01	0.119	18.46	0.03	0.32	0.03	0.01	<0.01	1.68	0.058	0.257	0.018	0.65	0.78	N.A.
646995	Drill Core	1.73	<0.01	0.144	18.61	0.03	0.96	0.01	0.01	<0.01	0.70	0.048	0.157	0.012	0.44	0.93	N.A.
646996	Drill Core	0.91	<0.01	0.224	21.02	0.02	0.26	<0.01	<0.01	<0.01	0.73	0.065	0.174	0.013	0.54	1.14	N.A.
646997	Drill Core	6.83	0.02	0.126	15.11	0.07	1.58	0.04	0.09	<0.01	0.38	0.019	0.118	0.009	0.34	0.98	N.A.
646998	Drill Core	4.67	0.01	0.138	15.63	0.07	1.72	0.20	0.93	<0.01	0.42	0.022	0.104	0.008	0.21	0.36	N.A.
646999	Drill Core	2.34	<0.01	0.101	17.31	0.02	0.14	0.02	<0.01	<0.01	0.54	0.029	0.126	0.010	0.34	0.70	N.A.
647000	Rock Pulp	0.71	0.01	0.150	22.55	0.02	0.30	<0.01	0.07	<0.01	1.08	0.032	0.233	0.013	0.87	2.23	N.A.
647001	Rock Pulp	4.03	<0.01	0.835	12.22	0.16	3.63	0.30	0.10	<0.01	0.35	0.057	0.185	0.007	0.30	0.23	N.A.
647002	Drill Core	0.67	<0.01	0.237	22.50	0.01	0.10	<0.01	<0.01	<0.01	0.75	0.044	0.117	0.011	0.44	1.12	N.A.
647003	Drill Core	0.65	<0.01	0.360	23.32	0.01	0.17	<0.01	<0.01	<0.01	0.56	0.045	0.153	0.009	0.48	1.60	N.A.
647004	Drill Core	0.94	0.01	0.211	22.24	0.06	0.39	<0.01	0.08	<0.01	0.05	0.002	0.082	0.005	0.34	1.72	N.A.
647005	Drill Core	0.19	<0.01	0.186	23.50	<0.01	0.06	<0.01	<0.01	<0.01	0.02	<0.001	0.058	0.004	0.46	1.94	N.A.
647006	Drill Core	0.97	0.01	0.147	21.39	0.03	0.56	0.11	0.13	<0.01	0.04	<0.001	0.067	0.004	0.37	1.69	N.A.
647007	Drill Core	3.41	0.07	0.083	9.08	0.24	5.78	2.39	1.10	<0.01	0.03	0.009	0.023	0.002	0.19	0.45	N.A.
647008	Drill Core	0.64	<0.01	0.195	22.37	0.03	0.39	0.03	0.06	<0.01	0.06	0.005	0.089	0.006	0.60	2.27	N.A.
647009	Drill Core	0.46	<0.01	0.199	22.11	<0.01	0.06	<0.01	<0.01	<0.01	0.09	0.012	0.128	0.007	0.60	2.63	N.A.
647010	Drill Core	1.90	0.01	<0.001	0.29	0.06	7.46	3.44	1.05	<0.01	<0.01	<0.001	<0.001	<0.001	0.05	0.05	N.A.
647011	Drill Core	1.10	0.01	0.157	20.31	0.01	0.32	<0.01	0.09	<0.01	0.21	0.006	0.167	0.008	0.41	0.91	N.A.
647012	Drill Core	1.76	<0.01	0.162	19.94	0.02	0.11	0.01	<0.01	<0.01	0.24	0.005	0.171	0.007	0.33	0.96	2.88
647013	Drill Core	1.64	<0.01	0.150	22.02	0.02	0.11	<0.01	<0.01	<0.01	0.20	0.006	0.163	0.007	0.42	1.58	N.A.
647014	Drill Core	1.24	<0.01	0.122	17.29	0.05	0.48	0.04	0.13	<0.01	0.53	0.009	0.149	0.008	0.35	0.63	N.A.
647015	Drill Core	1.40	<0.01	0.141	16.98	0.05	0.37	0.10	0.05	<0.01	0.43	0.010	0.112	0.006	0.32	0.45	N.A.
647016	Drill Core	1.11	<0.01	0.158	20.60	0.02	0.17	0.03	<0.01	<0.01	0.78	0.033	0.201	0.010	0.66	1.55	N.A.
647017	Drill Core	3.02	0.02	0.185	19.13	0.07	0.75	0.03	0.03	<0.01	0.27	0.013	0.148	0.008	0.59	2.16	N.A.
647018	Drill Core	5.19	<0.01	0.145	19.91	0.04	0.22	0.02	<0.01	<0.01	0.28	0.006	0.140	0.008	0.31	0.63	N.A.
647019	Drill Core	2.13	<0.01	0.146	19.33	0.02	0.11	0.02	<0.01	<0.01	0.74	0.012	0.184	0.010	0.71	1.48	N.A.
647020	Drill Core	3.20	<0.01	0.159	19.60	0.02	0.11	0.03	<0.01	<0.01	1.25	0.030	0.201	0.015	0.77	1.26	N.A.
647021	Drill Core	2.05	<0.01	0.118	20.19	0.02	0.18	0.01	<0.01	<0.01	0.77	0.016	0.218	0.012	0.64	1.52	N.A.
647022	Drill Core	1.31	<0.01	0.144	21.24	0.01	0.09	0.01	<0.01	<0.01	0.86	0.015	0.156	0.009	0.73	2.38	N.A.
647023	Drill Core	0.45	<0.01	0.158	22.54	0.01	0.09	<0.01	<0.01	<0.01	1.73	0.029	0.283	0.022	0.95	1.56	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: November 06, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000879.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
647024	Drill Core	10.59	3	6	12	1.58	<0.001	0.030	<0.02	<0.01	<2	0.269	0.019	0.13	9.95	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647025	Rock Pulp	0.04	I.S.	I.S.	I.S.	0.42	<0.001	0.052	<0.02	0.02	<2	0.230	0.011	0.11	8.69	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
647026	Rock Pulp	0.02	I.S.	I.S.	I.S.	4.07	<0.001	0.045	<0.02	<0.01	<2	0.393	0.025	0.12	12.31	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647027	Drill Core	10.05	3	27	27	1.08	<0.001	0.018	<0.02	<0.01	<2	0.302	0.016	0.12	9.58	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647028	Drill Core	8.67	7	28	30	0.71	<0.001	0.019	<0.02	<0.01	<2	0.281	0.013	0.11	7.67	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647029	Drill Core	9.32	<2	10	17	0.43	<0.001	0.052	<0.02	<0.01	<2	0.227	0.013	0.10	8.19	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647030A	Drill Core	8.54	<2	20	25	0.22	<0.001	0.027	<0.02	<0.01	<2	0.221	0.011	0.09	7.71	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647030B	Client Dup		<2	10	20	0.25	<0.001	0.032	<0.02	<0.01	<2	0.232	0.011	0.09	7.97	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647031	Drill Core	10.30	<2	19	28	0.85	<0.001	0.034	<0.02	<0.01	<2	0.313	0.017	0.11	8.68	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647032	Drill Core	9.83	<2	18	22	1.00	<0.001	0.030	<0.02	<0.01	<2	0.217	0.016	0.08	9.68	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647033	Drill Core	9.53	<2	19	25	0.93	<0.001	0.035	<0.02	<0.01	<2	0.256	0.015	0.11	8.55	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647034	Drill Core	9.91	<2	68	79	1.89	<0.001	0.038	<0.02	<0.01	<2	0.307	0.020	0.11	11.04	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647035	Drill Core	9.77	<2	12	13	1.12	<0.001	0.023	<0.02	<0.01	<2	0.235	0.016	0.13	9.11	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647036	Drill Core	9.94	<2	17	20	1.27	<0.001	0.022	<0.02	<0.01	<2	0.226	0.016	0.11	8.82	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647037	Drill Core	9.57	14	14	17	1.63	<0.001	0.040	<0.02	<0.01	<2	0.237	0.018	0.11	9.94	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647038	Drill Core	8.24	15	21	43	2.22	<0.001	0.039	<0.02	<0.01	<2	0.258	0.021	0.11	10.79	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647039	Drill Core	6.29	<2	6	12	1.51	<0.001	0.036	<0.02	<0.01	<2	0.210	0.016	0.10	9.52	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647040	Drill Core	2.14	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.001	<0.001	0.07	1.11	<0.02	0.07	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: November 06, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000879.1

Method		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
Unit		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
MDL		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
647024	Drill Core	0.19	<0.01	0.101	23.63	<0.01	0.05	<0.01	<0.01	<0.01	1.25	0.029	0.243	0.015	0.86	1.90	N.A.
647025	Rock Pulp	4.25	<0.01	0.993	13.16	0.18	4.03	0.33	0.10	<0.01	0.39	0.057	0.185	0.007	0.29	0.23	N.A.
647026	Rock Pulp	1.13	0.01	0.181	19.58	0.02	0.27	0.03	0.09	<0.01	2.80	0.049	0.405	0.024	1.11	1.45	N.A.
647027	Drill Core	0.27	0.01	0.095	23.98	0.01	0.17	<0.01	<0.01	<0.01	0.95	0.020	0.262	0.013	1.95	4.96	N.A.
647028	Drill Core	0.08	<0.01	0.153	23.79	<0.01	0.07	<0.01	<0.01	<0.01	0.68	0.021	0.254	0.012	1.31	4.96	N.A.
647029	Drill Core	0.43	0.01	0.197	23.34	0.01	0.10	<0.01	<0.01	<0.01	0.51	0.033	0.191	0.012	0.93	4.92	N.A.
647030A	Drill Core	0.26	0.01	0.188	23.50	0.02	0.12	<0.01	<0.01	<0.01	0.32	0.026	0.195	0.010	0.73	5.31	N.A.
647030B	Client Dup	0.25	<0.01	0.182	23.32	0.02	0.12	<0.01	<0.01	<0.01	0.35	0.030	0.203	0.011	0.78	5.10	N.A.
647031	Drill Core	0.80	<0.01	0.202	23.53	0.02	0.14	<0.01	<0.01	<0.01	0.75	0.039	0.282	0.016	1.24	3.46	N.A.
647032	Drill Core	0.21	<0.01	0.204	23.40	<0.01	0.11	<0.01	<0.01	<0.01	0.84	0.032	0.211	0.016	1.03	3.63	3.01
647033	Drill Core	0.67	<0.01	0.277	23.71	0.01	0.11	<0.01	<0.01	<0.01	0.86	0.038	0.231	0.015	1.15	3.88	N.A.
647034	Drill Core	0.32	<0.01	0.212	22.12	0.02	0.23	<0.01	<0.01	<0.01	1.47	0.040	0.304	0.022	1.33	3.67	N.A.
647035	Drill Core	0.10	<0.01	0.258	25.06	<0.01	0.11	<0.01	<0.01	<0.01	1.02	0.024	0.206	0.015	1.12	4.26	N.A.
647036	Drill Core	0.12	0.01	0.218	22.54	<0.01	0.19	<0.01	0.03	<0.01	1.01	0.025	0.216	0.017	1.11	3.69	N.A.
647037	Drill Core	0.30	<0.01	0.212	22.58	0.01	0.10	<0.01	<0.01	<0.01	1.31	0.043	0.235	0.019	1.20	3.94	N.A.
647038	Drill Core	0.44	<0.01	0.172	22.68	0.01	0.09	<0.01	<0.01	<0.01	1.62	0.042	0.256	0.023	1.38	3.22	N.A.
647039	Drill Core	0.30	<0.01	0.229	21.05	0.02	0.14	<0.01	<0.01	<0.01	1.05	0.043	0.236	0.019	1.78	5.21	N.A.
647040	Drill Core	1.90	0.02	0.002	0.28	0.07	7.27	3.52	1.04	<0.01	<0.01	<0.001	0.001	<0.001	0.09	0.06	N.A.

QUALITY CONTROL REPORT

SMI08000879.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
Pulp Duplicates																					
REP G1	QC				0.03																
646994	Drill Core	10.26	3	42	29	2.45	<0.001	0.054	<0.02	<0.01	<2	0.256	0.017	0.14	11.00	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
REP 646994	QC		5	38	30																
647001	Rock Pulp	0.02	I.S.	I.S.	I.S.	0.47	<0.001	0.048	<0.02	0.02	<2	0.218	0.010	0.10	8.32	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
REP 647001	QC					<0.001	0.052	<0.02	0.02	<2	0.234	0.011	0.11	9.22	<0.02	<0.01	<0.001	<0.01	<0.01	0.02	
REP 647024	QC																				
647033	Drill Core	9.53	<2	19	25	0.93	<0.001	0.035	<0.02	<0.01	<2	0.256	0.015	0.11	8.55	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 647033	QC					<0.001	0.036	<0.02	<0.01	<2	0.258	0.015	0.11	8.65	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	
647036	Drill Core	9.94	<2	17	20	1.27	<0.001	0.022	<0.02	<0.01	<2	0.226	0.016	0.11	8.82	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 647036	QC		<2	18	17																
647038	Drill Core	8.24	15	21	43	2.22	<0.001	0.039	<0.02	<0.01	<2	0.258	0.021	0.11	10.79	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 647038	QC																				
Core Reject Duplicates																					
647024	Drill Core	10.59	3	6	12	1.58	<0.001	0.030	<0.02	<0.01	<2	0.269	0.019	0.13	9.95	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
DUP 647024	QC		<2	15	11	1.66	<0.001	0.028	<0.02	<0.01	<2	0.258	0.018	0.13	9.60	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
Reference Materials																					
STD CDN-PGMS-14	Standard		248	106	405																
STD CDN-PGMS-14	Standard		233	109	431																
STD CSC	Standard					4.13															
STD CSC	Standard					4.03															
STD FA10R	Standard		500	484	503																
STD FA10R	Standard		478	451	489																
STD FA10R	Standard		476	445	486																
STD FA10R	Standard		436	443	443																
STD OREAS76A	Standard					16.89															
STD OREAS76A	Standard					17.80															
STD R4T	Standard					0.062	0.488	1.53	3.33	86	0.356	0.040	0.09	23.53	<0.02	0.02	0.018	0.01	<0.01	0.02	
STD R4T	Standard					0.062	0.515	1.55	3.57	87	0.353	0.040	0.09	24.95	<0.02	0.02	0.018	0.01	<0.01	0.02	

QUALITY CONTROL REPORT

SMI08000879.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
Pulp Duplicates																	
REP G1	QC																
646994	Drill Core	3.13	0.01	0.119	18.46	0.03	0.32	0.03	0.01	<0.01	1.68	0.058	0.257	0.018	0.65	0.78	N.A.
REP 646994	QC																
647001	Rock Pulp	4.03	<0.01	0.835	12.22	0.16	3.63	0.30	0.10	<0.01	0.35	0.057	0.185	0.007	0.30	0.23	N.A.
REP 647001	QC	4.31	<0.01	1.062	13.18	0.18	4.13	0.32	0.10	<0.01	0.37	0.055	0.178	0.007	0.29	0.21	
REP 647024	QC											0.028	0.236	0.014	0.80	1.68	
647033	Drill Core	0.67	<0.01	0.277	23.71	0.01	0.11	<0.01	<0.01	<0.01	0.86	0.038	0.231	0.015	1.15	3.88	N.A.
REP 647033	QC	0.66	<0.01	0.264	24.09	0.01	0.11	<0.01	<0.01	<0.01	0.88						
647036	Drill Core	0.12	0.01	0.218	22.54	<0.01	0.19	<0.01	0.03	<0.01	1.01	0.025	0.216	0.017	1.11	3.69	N.A.
REP 647036	QC																
647038	Drill Core	0.44	<0.01	0.172	22.68	0.01	0.09	<0.01	<0.01	<0.01	1.62	0.042	0.256	0.023	1.38	3.22	N.A.
REP 647038	QC											0.041	0.252	0.023	1.35	3.12	
Core Reject Duplicates																	
647024	Drill Core	0.19	<0.01	0.101	23.63	<0.01	0.05	<0.01	<0.01	<0.01	1.25	0.029	0.243	0.015	0.86	1.90	N.A.
DUP 647024	QC	0.21	<0.01	0.096	23.14	<0.01	0.05	<0.01	<0.01	<0.01	1.14	0.029	0.241	0.014	0.84	1.77	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																
STD OREAS76A	Standard																
STD R4T	Standard	2.07	0.05	0.017	1.34	0.18	3.77	0.86	1.12	<0.01	10.90						
STD R4T	Standard	2.18	0.04	0.018	1.44	0.21	4.00	0.92	1.14	<0.01	12.18						

QUALITY CONTROL REPORT

SMI08000879.1

		WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD		
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
STD SF-3A_NI	Standard																					
STD SF-3A_NI	Standard																					
STD SF-3T	Standard					0.031	0.748	0.86	1.06	50	0.341	0.016	0.40	8.07	<0.02	0.04	0.004	<0.01	<0.01	0.01		
STD SF-3T	Standard					0.031	0.760	0.87	1.09	53	0.351	0.016	0.38	8.16	<0.02	0.04	0.004	<0.01	<0.01	0.01		
STD SF-3T Expected						0.032	0.7723	0.961	1.0672	52	0.35	0.0181	0.432	8.33	0.004	0.044	0.00475	0.00111	0.00048	0.0143		
STD R4T Expected						0.062	0.502	1.518	3.376	86	0.348	0.039	0.086	24.07	0.0087	0.0185	0.018	0.0138	0.0018	0.016		
STD CDN-PGMS-14			259	119	451																	
STD FA10R Expected			485	472	476																	
STD CSC Expected						4.25																
STD OREAS76A Expected						18																
STD SF-3A_NI Expected																						
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01		
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01		
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
BLK	Blank					<0.02																
BLK	Blank					<0.02																
BLK	Blank																					
BLK	Blank																					
Prep Wash																						
G1	Prep Blank	<0.01	<2	<3	10	<0.02	<0.001	0.001	<0.02	<0.01	<2	<0.001	<0.001	0.08	2.56	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	
G1	Prep Blank	<0.01	<2	<3	<2		<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.38	<0.02	0.07	<0.001	<0.01	<0.01	<0.01	
G1	Prep Blank					0.04																

QUALITY CONTROL REPORT

SMI08000879.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
STD SF-3A_NI	Standard											0.796	0.313	0.015	1.51	1.97	
STD SF-3A_NI	Standard											0.009	0.341	0.018	3.89	3.48	
STD SF-3T	Standard	3.96	0.04	0.017	4.38	0.19	5.25	2.01	2.40	<0.01	3.63						
STD SF-3T	Standard	4.01	0.05	0.018	4.51	0.19	5.32	2.04	2.44	<0.01	3.72						
STD SF-3T Expected		4.1	0.06	0.02074	4.67	0.19	5.43	2.06	2.47	0.00043	3.5						
STD R4T Expected		2.166	0.045	0.018	1.384		3.897	0.9	1.153	0.00016							
STD CDN-PGMS-14																	
STD FA10R Expected																	
STD CSC Expected																	
STD OREAS76A Expected																	
STD SF-3A_NI Expected												0.3205					
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
Prep Wash																	
G1	Prep Blank	2.58	0.09	<0.001	0.69	0.25	7.94	2.70	2.93	<0.01	0.02	<0.001	<0.001	<0.001	0.06	0.03	N.A.
G1	Prep Blank	2.45	0.08	<0.001	0.66	0.23	7.68	2.55	2.86	<0.01	<0.01	<0.001	<0.001	<0.001	0.04	0.02	N.A.
G1	Prep Blank																

Hole 08-261



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Email Distribution List
 Receiving Lab: Canada-Smithers
 Received: September 02, 2008
 Report Date: October 25, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000852.1

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-261A
 P.O. Number
 Number of Samples: 48

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC: Email Distribution List

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	44	Crush split and pulverize drill core to 200 mesh		
3B	44	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	48	Analysis by Leco	0.1	Completed
7TD	48	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	48	Leached with H2O2 + NH4 citrate	1	Completed
Specific Gravity	4	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.
 All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.
 "**" asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 25, 2008

Page: 2 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000852.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
647041	Drill Core	6.29	<2	<3	2	0.06	<0.001	0.001	<0.02	<0.01	<2	0.283	0.011	0.09	5.26	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647042	Drill Core	9.63	<2	<3	8	0.09	<0.001	0.001	<0.02	<0.01	3	0.278	0.011	0.10	5.56	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647043	Drill Core	9.80	<2	<3	<2	0.06	<0.001	<0.001	<0.02	<0.01	<2	0.315	0.012	0.09	5.22	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647044	Drill Core	9.84	<2	11	10	0.09	<0.001	<0.001	<0.02	<0.01	<2	0.308	0.012	0.09	5.34	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647045	Drill Core	9.89	<2	4	6	0.10	<0.001	0.004	<0.02	<0.01	<2	0.296	0.012	0.09	5.23	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647046	Drill Core	9.30	<2	<3	<2	0.08	<0.001	0.003	<0.02	<0.01	3	0.305	0.011	0.08	4.56	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647047	Drill Core	10.06	<2	6	3	0.08	<0.001	0.002	<0.02	<0.01	<2	0.217	0.011	0.09	5.46	<0.02	0.01	<0.001	<0.01	<0.01	<0.01
647048	Drill Core	9.46	<2	10	11	0.10	<0.001	0.002	<0.02	<0.01	3	0.223	0.012	0.11	6.28	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647049	Drill Core	9.99	2	10	10	0.07	<0.001	0.003	<0.02	<0.01	4	0.274	0.012	0.10	5.64	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647050	Rock Pulp	0.04	I.S.	I.S.	I.S.	4.12	<0.001	0.048	<0.02	<0.01	2	0.412	0.027	0.12	12.65	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647051	Rock Pulp	0.04	I.S.	I.S.	I.S.	0.45	<0.001	0.056	<0.02	0.02	4	0.239	0.012	0.11	8.94	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
647052	Drill Core	9.51	2	<3	23	0.15	<0.001	0.004	<0.02	<0.01	3	0.337	0.013	0.09	5.51	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647053	Drill Core	8.87	<2	10	12	0.11	<0.001	0.004	<0.02	<0.01	<2	0.293	0.013	0.09	5.38	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647054	Drill Core	9.75	<2	<3	4	0.03	<0.001	0.001	<0.02	<0.01	<2	0.319	0.012	0.09	4.96	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647055	Drill Core	10.11	<2	24	20	0.06	<0.001	0.002	<0.02	<0.01	<2	0.302	0.013	0.09	5.17	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647056	Drill Core	9.74	<2	5	2	0.05	<0.001	<0.001	<0.02	<0.01	<2	0.254	0.013	0.10	5.72	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647057	Drill Core	9.49	<2	16	13	0.10	<0.001	0.002	<0.02	<0.01	<2	0.291	0.013	0.10	5.52	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647058	Drill Core	9.06	<2	7	5	0.12	<0.001	0.002	<0.02	<0.01	<2	0.298	0.012	0.10	5.08	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647059	Drill Core	8.30	<2	47	42	0.22	<0.001	0.005	<0.02	<0.01	<2	0.310	0.012	0.09	5.02	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647060A	Drill Core	8.79	5	14	17	0.13	<0.001	0.002	<0.02	<0.01	<2	0.255	0.011	0.12	6.01	<0.02	0.05	<0.001	<0.01	<0.01	<0.01
647060B	Client Dup		<2	15	12	0.14	<0.001	0.002	<0.02	<0.01	<2	0.257	0.011	0.13	5.97	<0.02	0.05	<0.001	<0.01	<0.01	<0.01
647061	Drill Core	8.57	<2	9	7	0.16	<0.001	0.003	<0.02	<0.01	<2	0.270	0.012	0.10	5.47	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647062	Drill Core	8.34	<2	12	13	0.26	<0.001	0.010	<0.02	<0.01	<2	0.278	0.012	0.12	6.02	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647063	Drill Core	8.14	<2	24	23	0.25	<0.001	0.018	<0.02	<0.01	<2	0.238	0.011	0.10	5.96	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647064	Drill Core	4.87	<2	24	27	0.26	<0.001	0.035	<0.02	<0.01	<2	0.253	0.013	0.11	6.15	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647065	Drill Core	4.76	<2	45	54	0.50	<0.001	0.029	<0.02	0.01	<2	0.238	0.013	0.12	6.19	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647066	Drill Core	8.62	<2	50	72	0.83	0.004	0.047	<0.02	<0.01	<2	0.085	0.007	0.11	5.36	<0.02	0.04	<0.001	<0.01	<0.01	<0.01
647067	Drill Core	9.24	<2	66	80	0.23	<0.001	0.033	<0.02	0.01	<2	0.140	0.013	0.11	6.40	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647068	Drill Core	8.13	<2	109	126	0.28	<0.001	0.069	<0.02	<0.01	<2	0.292	0.016	0.11	6.54	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647069	Drill Core	8.61	<2	<3	8	0.16	<0.001	0.004	<0.02	<0.01	<2	0.240	0.013	0.10	6.49	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 25, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000852.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S		Cu	Ni	Co	Fe	Mg	SG
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
647041	Drill Core	0.66	0.02	0.134	26.92	0.03	0.49	<0.01	0.06	<0.01	0.08	0.001	0.075	0.004	0.46	1.93	N.A.
647042	Drill Core	1.07	0.02	0.166	25.30	0.07	0.61	<0.01	0.10	<0.01	0.10	0.002	0.086	0.004	0.48	2.06	N.A.
647043	Drill Core	0.27	0.01	0.201	28.44	<0.01	0.08	<0.01	<0.01	<0.01	0.07	<0.001	0.080	0.004	0.51	2.29	N.A.
647044	Drill Core	0.37	<0.01	0.187	27.68	0.01	0.09	<0.01	0.01	<0.01	0.10	0.001	0.113	0.004	0.45	2.04	N.A.
647045	Drill Core	0.32	<0.01	0.246	28.11	0.01	0.10	<0.01	<0.01	<0.01	0.10	0.001	0.115	0.005	0.56	2.67	N.A.
647046	Drill Core	0.14	<0.01	0.157	28.18	<0.01	0.08	<0.01	<0.01	<0.01	0.07	<0.001	0.095	0.004	0.52	2.75	N.A.
647047	Drill Core	1.26	0.02	0.112	24.95	0.06	1.16	0.09	0.40	<0.01	0.12	0.002	0.096	0.005	0.44	1.98	N.A.
647048	Drill Core	0.95	0.02	0.167	25.73	0.07	0.65	0.04	0.17	<0.01	0.10	0.002	0.095	0.005	0.50	2.09	N.A.
647049	Drill Core	0.19	<0.01	0.111	28.35	<0.01	0.06	<0.01	<0.01	<0.01	0.08	0.003	0.088	0.004	0.53	2.38	N.A.
647050	Rock Pulp	1.14	0.01	0.187	20.97	0.02	0.28	0.03	0.10	<0.01	3.03	0.049	0.383	0.024	1.15	1.70	N.A.
647051	Rock Pulp	4.19	0.02	1.175	13.53	0.18	4.13	0.33	0.12	<0.01	0.52	0.057	0.180	0.007	0.33	0.30	N.A.
647052	Drill Core	0.14	<0.01	0.143	27.73	<0.01	0.06	<0.01	<0.01	<0.01	0.13	0.004	0.148	0.006	0.55	2.60	2.93
647053	Drill Core	0.14	<0.01	0.160	26.50	<0.01	0.06	<0.01	<0.01	<0.01	0.12	0.004	0.126	0.006	0.63	3.10	N.A.
647054	Drill Core	0.22	<0.01	0.250	28.37	<0.01	0.06	<0.01	<0.01	<0.01	0.08	0.001	0.063	0.003	0.61	2.78	N.A.
647055	Drill Core	0.37	<0.01	0.244	26.27	0.01	0.08	<0.01	<0.01	<0.01	0.07	0.002	0.080	0.004	0.68	2.92	N.A.
647056	Drill Core	0.52	<0.01	0.173	25.95	0.01	0.08	<0.01	<0.01	<0.01	0.07	0.001	0.073	0.004	0.58	2.56	N.A.
647057	Drill Core	0.70	<0.01	0.104	25.72	0.03	0.36	<0.01	0.09	<0.01	0.11	0.002	0.099	0.005	0.56	2.44	N.A.
647058	Drill Core	0.68	<0.01	0.099	26.12	0.01	0.07	<0.01	<0.01	<0.01	0.11	0.002	0.111	0.005	0.49	2.47	N.A.
647059	Drill Core	1.07	0.01	0.094	24.91	0.04	0.30	<0.01	<0.01	<0.01	0.25	0.004	0.225	0.008	0.38	2.50	N.A.
647060A	Drill Core	2.19	0.03	0.100	23.16	0.09	0.82	<0.01	<0.01	<0.01	0.16	0.002	0.146	0.005	0.26	1.45	N.A.
647060B	Client Dup	2.44	0.04	0.100	23.64	0.10	0.91	<0.01	<0.01	<0.01	0.16	0.002	0.138	0.005	0.23	1.33	N.A.
647061	Drill Core	0.28	<0.01	0.175	25.93	0.01	0.09	<0.01	<0.01	<0.01	0.19	<0.001	0.181	0.008	0.68	6.17	N.A.
647062	Drill Core	1.12	<0.01	0.179	23.90	0.02	0.27	<0.01	<0.01	<0.01	0.26	0.010	0.224	0.008	0.57	3.19	2.91
647063	Drill Core	0.77	<0.01	0.222	21.92	0.02	0.17	<0.01	<0.01	<0.01	0.27	0.018	0.240	0.010	0.51	3.27	N.A.
647064	Drill Core	0.85	<0.01	0.154	21.88	0.04	0.61	<0.01	<0.01	<0.01	0.28	0.032	0.245	0.011	0.48	2.18	N.A.
647065	Drill Core	1.06	<0.01	0.126	21.40	0.03	1.18	0.02	0.38	<0.01	0.49	0.026	0.232	0.011	0.63	2.61	N.A.
647066	Drill Core	2.50	0.07	0.089	9.53	0.21	6.00	2.65	1.48	<0.01	0.83	0.048	0.080	0.005	0.65	0.54	N.A.
647067	Drill Core	0.70	<0.01	0.108	20.71	0.03	1.02	0.02	0.50	<0.01	0.25	0.031	0.122	0.010	0.33	1.28	N.A.
647068	Drill Core	0.10	<0.01	0.167	26.91	<0.01	0.05	<0.01	<0.01	<0.01	0.31	0.062	0.273	0.013	0.46	4.41	N.A.
647069	Drill Core	0.23	<0.01	0.194	26.18	0.02	0.30	<0.01	<0.01	<0.01	0.19	0.004	0.232	0.011	0.42	3.59	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 25, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000852.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
647070	Drill Core	2.14	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.08	1.08	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
647071	Drill Core	9.17	<2	<3	5	0.18	<0.001	0.003	<0.02	<0.01	<2	0.251	0.013	0.12	5.77	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647072	Drill Core	9.37	<2	7	4	0.15	<0.001	0.001	<0.02	<0.01	<2	0.229	0.014	0.10	6.46	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647073	Drill Core	9.11	<2	<3	2	0.17	<0.001	0.003	<0.02	<0.01	<2	0.231	0.012	0.09	6.04	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647074	Drill Core	8.51	<2	6	8	0.17	<0.001	0.003	<0.02	<0.01	<2	0.244	0.012	0.11	5.68	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647075	Rock Pulp	0.06	I.S.	I.S.	I.S.	1.32	<0.001	0.032	<0.02	0.01	<2	0.271	0.018	0.13	9.13	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647076	Rock Pulp	0.01	I.S.	I.S.	I.S.	0.43	<0.001	0.056	<0.02	0.02	<2	0.244	0.012	0.12	8.85	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
647077	Drill Core	8.98	3	4	5	0.18	<0.001	0.004	<0.02	<0.01	<2	0.241	0.012	0.10	5.57	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647078	Drill Core	8.89	<2	5	6	0.18	<0.001	0.014	<0.02	<0.01	<2	0.242	0.012	0.12	5.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647079	Drill Core	8.91	<2	5	5	0.12	<0.001	0.004	<0.02	<0.01	<2	0.186	0.010	0.13	6.15	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647080	Drill Core	6.83	<2	6	5	0.13	<0.001	0.007	<0.02	<0.01	<2	0.204	0.011	0.11	5.99	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647081	Drill Core	8.79	<2	10	14	0.90	<0.001	0.024	<0.02	<0.01	<2	0.191	0.015	0.11	7.83	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647082	Drill Core	8.88	4	8	19	0.90	<0.001	0.025	<0.02	<0.01	<2	0.201	0.018	0.08	6.85	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647083	Drill Core	9.03	<2	20	25	0.93	<0.001	0.023	<0.02	<0.01	<2	0.226	0.015	0.09	7.15	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647084	Drill Core	9.23	3	37	44	0.52	<0.001	0.019	<0.02	0.01	<2	0.197	0.011	0.16	8.64	<0.02	0.05	<0.001	<0.01	<0.01	0.02
647085	Drill Core	8.79	2	18	24	0.52	<0.001	0.015	<0.02	<0.01	<2	0.188	0.010	0.11	6.67	<0.02	0.02	<0.001	<0.01	<0.01	<0.01
647086	Drill Core	8.63	3	19	17	0.67	<0.001	0.021	<0.02	<0.01	<2	0.248	0.014	0.11	7.95	<0.02	0.02	<0.001	<0.01	<0.01	<0.01
647087	Drill Core	9.01	6	47	51	1.27	<0.001	0.034	<0.02	<0.01	<2	0.333	0.021	0.15	8.83	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 25, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000852.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
647070	Drill Core	1.91	0.02	0.001	0.25	0.08	6.76	3.50	1.23	<0.01	<0.01	<0.001	<0.001	<0.001	0.08	0.04	N.A.
647071	Drill Core	0.38	<0.01	0.179	25.21	<0.01	0.09	<0.01	<0.01	<0.01	0.18	0.004	0.251	0.011	0.41	3.60	N.A.
647072	Drill Core	0.08	<0.01	0.204	25.10	<0.01	0.06	<0.01	<0.01	<0.01	0.16	0.002	0.223	0.011	0.36	3.44	2.77
647073	Drill Core	0.14	<0.01	0.193	25.07	<0.01	0.06	<0.01	<0.01	<0.01	0.18	0.002	0.232	0.011	0.39	4.04	N.A.
647074	Drill Core	0.25	<0.01	0.178	24.62	<0.01	0.05	<0.01	<0.01	<0.01	0.18	0.003	0.258	0.011	0.43	3.84	N.A.
647075	Rock Pulp	0.73	<0.01	0.151	24.63	0.02	0.32	<0.01	0.07	<0.01	1.22	0.031	0.238	0.013	1.25	3.51	N.A.
647076	Rock Pulp	4.33	<0.01	1.060	13.49	0.19	4.03	0.32	0.11	<0.01	0.52	0.061	0.210	0.008	0.57	0.53	N.A.
647077	Drill Core	0.24	<0.01	0.195	23.78	<0.01	0.05	<0.01	<0.01	<0.01	0.18	0.005	0.258	0.012	0.50	4.36	N.A.
647078	Drill Core	1.02	0.01	0.150	23.62	0.04	0.64	<0.01	<0.01	<0.01	0.21	0.014	0.250	0.010	0.44	3.11	N.A.
647079	Drill Core	0.63	0.02	0.125	22.35	0.13	1.80	<0.01	<0.01	<0.01	0.17	0.004	0.167	0.007	0.31	1.33	N.A.
647080	Drill Core	1.13	<0.01	0.155	20.92	0.04	1.39	0.02	0.94	<0.01	0.19	0.008	0.184	0.008	0.39	1.29	N.A.
647081	Drill Core	0.50	0.02	0.104	21.89	0.05	0.40	<0.01	0.27	<0.01	0.83	0.024	0.193	0.014	0.90	1.55	N.A.
647082	Drill Core	0.74	<0.01	0.114	21.26	0.02	0.31	<0.01	<0.01	<0.01	0.88	0.026	0.226	0.018	0.95	2.23	2.70
647083	Drill Core	1.84	<0.01	0.150	21.81	<0.01	0.12	<0.01	<0.01	<0.01	0.88	0.023	0.252	0.015	0.89	2.54	N.A.
647084	Drill Core	3.42	0.06	0.144	15.35	0.22	3.58	0.27	1.35	<0.01	0.56	0.018	0.189	0.008	0.50	0.70	N.A.
647085	Drill Core	1.65	0.04	0.071	18.64	0.11	2.47	1.01	0.54	<0.01	0.66	0.014	0.194	0.009	0.73	2.30	N.A.
647086	Drill Core	1.58	0.02	0.107	21.99	0.09	1.34	<0.01	0.25	<0.01	0.73	0.020	0.249	0.012	0.88	2.69	N.A.
647087	Drill Core	0.77	<0.01	0.108	23.93	<0.01	0.05	<0.01	<0.01	<0.01	1.26	0.033	0.348	0.019	1.27	4.05	N.A.

QUALITY CONTROL REPORT

SMI08000852.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
Pulp Duplicates																					
REP G1	QC	<0.02																			
647048	Drill Core	9.46	<2	10	11	0.10	<0.001	0.002	<0.02	<0.01	3	0.223	0.012	0.11	6.28	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 647048	QC	3 8 13																			
647056	Drill Core	9.74	<2	5	2	0.05	<0.001	<0.001	<0.02	<0.01	<2	0.254	0.013	0.10	5.72	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 647056	QC																				
647064	Drill Core	4.87	<2	24	27	0.26	<0.001	0.035	<0.02	<0.01	<2	0.253	0.013	0.11	6.15	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 647064	QC	<2 21 23																			
647074	Drill Core	8.51	<2	6	8	0.17	<0.001	0.003	<0.02	<0.01	<2	0.244	0.012	0.11	5.68	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 647074	QC																				
647084	Drill Core	9.23	3	37	44	0.52	<0.001	0.019	<0.02	0.01	<2	0.197	0.011	0.16	8.64	<0.02	0.05	<0.001	<0.01	<0.01	0.02
REP 647084	QC																				
647085	Drill Core	8.79	2	18	24	0.52	<0.001	0.015	<0.02	<0.01	<2	0.188	0.010	0.11	6.67	<0.02	0.02	<0.001	<0.01	<0.01	<0.01
REP 647085	QC	3 24 26																			
647086	Drill Core	8.63	3	19	17	0.67	<0.001	0.021	<0.02	<0.01	<2	0.248	0.014	0.11	7.95	<0.02	0.02	<0.001	<0.01	<0.01	<0.01
REP 647086	QC	<0.001 0.021 <0.02 <0.01 <2 0.246 0.013 0.10 7.89 <0.02 0.02 <0.001 <0.01 <0.01 <0.01																			
Core Reject Duplicates																					
647044	Drill Core	9.84	<2	11	10	0.09	<0.001	<0.001	<0.02	<0.01	<2	0.308	0.012	0.09	5.34	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
DUP 647044	QC	<2 13 12 0.08 <0.001 <0.001 <0.02 <0.01 <2 0.308 0.012 0.10 5.28 <0.02 <0.01 <0.001 <0.01 <0.01 <0.01																			
647078	Drill Core	8.89	<2	5	6	0.18	<0.001	0.014	<0.02	<0.01	<2	0.242	0.012	0.12	5.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
DUP 647078	QC	<2 5 7 0.16 <0.001 0.009 <0.02 <0.01 <2 0.241 0.012 0.11 5.72 <0.02 <0.01 <0.001 <0.01 <0.01 <0.01																			
Reference Materials																					
STD CDN-PGMS-14	Standard	259 111 440																			
STD CDN-PGMS-14	Standard	291 123 448																			
STD CSC	Standard	4.07																			
STD CSC	Standard	4.06																			
STD FA10R	Standard	471 463 472																			
STD FA10R	Standard	444 428 431																			
STD FA10R	Standard	478 427 466																			

QUALITY CONTROL REPORT

SMI08000852.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG	
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%		
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
Pulp Duplicates																	
REP G1	QC																
647048	Drill Core	0.95	0.02	0.167	25.73	0.07	0.65	0.04	0.17	<0.01	0.10	0.002	0.095	0.005	0.50	2.09	N.A.
REP 647048	QC																
647056	Drill Core	0.52	<0.01	0.173	25.95	0.01	0.08	<0.01	<0.01	<0.01	0.07	0.001	0.073	0.004	0.58	2.56	N.A.
REP 647056	QC										0.001	0.075	0.004	0.59	2.66		
647064	Drill Core	0.85	<0.01	0.154	21.88	0.04	0.61	<0.01	<0.01	<0.01	0.28	0.032	0.245	0.011	0.48	2.18	N.A.
REP 647064	QC																
647074	Drill Core	0.25	<0.01	0.178	24.62	<0.01	0.05	<0.01	<0.01	<0.01	0.18	0.003	0.258	0.011	0.43	3.84	N.A.
REP 647074	QC										0.003	0.255	0.011	0.42	3.76		
647084	Drill Core	3.42	0.06	0.144	15.35	0.22	3.58	0.27	1.35	<0.01	0.56	0.018	0.189	0.008	0.50	0.70	N.A.
REP 647084	QC										0.018	0.187	0.008	0.48	0.66		
647085	Drill Core	1.65	0.04	0.071	18.64	0.11	2.47	1.01	0.54	<0.01	0.66	0.014	0.194	0.009	0.73	2.30	N.A.
REP 647085	QC																
647086	Drill Core	1.58	0.02	0.107	21.99	0.09	1.34	<0.01	0.25	<0.01	0.73	0.020	0.249	0.012	0.88	2.69	N.A.
REP 647086	QC	1.56	0.02	0.101	21.73	0.09	1.35	<0.01	0.24	<0.01	0.72						
Core Reject Duplicates																	
647044	Drill Core	0.37	<0.01	0.187	27.68	0.01	0.09	<0.01	0.01	<0.01	0.10	0.001	0.113	0.004	0.45	2.04	N.A.
DUP 647044	QC	0.43	<0.01	0.187	27.78	0.01	0.09	<0.01	<0.01	<0.01	0.10	0.001	0.108	0.004	0.45	2.00	N.A.
647078	Drill Core	1.02	0.01	0.150	23.62	0.04	0.64	<0.01	<0.01	<0.01	0.21	0.014	0.250	0.010	0.44	3.11	N.A.
DUP 647078	QC	0.79	<0.01	0.174	23.84	0.03	0.59	<0.01	<0.01	<0.01	0.20	0.009	0.243	0.010	0.40	2.96	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CSC	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																

QUALITY CONTROL REPORT

SMI08000852.1

		WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
STD FA10R	Standard		450	446	464																
STD FA10R	Standard		466	460	481																
STD OREAS76A	Standard					17.06															
STD OREAS76A	Standard					17.52															
STD R3NI	Standard																				
STD R3NI	Standard																				
STD R4T	Standard					0.061	0.499	1.62	3.48	87	0.355	0.043	0.09	25.07	<0.02	0.02	0.019	<0.01	<0.01	0.02	
STD R4T	Standard					0.063	0.518	1.55	3.48	90	0.358	0.041	0.09	24.67	<0.02	0.02	0.018	0.02	<0.01	0.02	
STD SF-3A_NI	Standard																				
STD SF-3A_NI	Standard																				
STD SF-3T	Standard					0.032	0.799	0.95	1.09	55	0.361	0.019	0.44	8.37	<0.02	0.04	0.005	<0.01	<0.01	0.01	
STD SF-3T	Standard					0.031	0.809	0.92	1.11	53	0.349	0.018	0.43	8.26	<0.02	0.04	0.004	<0.01	<0.01	0.01	
STD SF-3T Expected						0.032	0.7723	0.961	1.0672	52	0.35	0.0181	0.432	8.33	0.004	0.044	0.00475	0.00111	0.00048	0.0143	
STD R4T Expected						0.062	0.502	1.518	3.376	86	0.348	0.039	0.086	24.07	0.0087	0.0185	0.018	0.0138	0.0018	0.016	
STD CDN-PGMS-14			259	119	451																
STD CSC Expected						4.25															
STD OREAS76A Expected						18															
STD FA10R Expected			485	472	476																
STD R3NI Expected																					
STD SF-3A_NI Expected																					
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	
BLK	Blank																				
BLK	Blank		<2	<3	<2																
BLK	Blank																				
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																

QUALITY CONTROL REPORT

SMI08000852.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																
STD OREAS76A	Standard																
STD R3NI	Standard											0.751	0.404	0.052	3.82	0.14	
STD R3NI	Standard											0.742	0.341	0.047	2.58	0.08	
STD R4T	Standard	2.23	0.05	0.021	1.43	0.21	3.74	0.89	1.15	<0.01	12.01						
STD R4T	Standard	2.20	0.05	0.018	1.42	0.20	3.99	0.91	1.18	<0.01	11.94						
STD SF-3A_NI	Standard											0.803	0.331	0.016	1.88	2.66	
STD SF-3A_NI	Standard											0.020	0.326	0.017	3.82	3.31	
STD SF-3T	Standard	4.16	0.05	0.021	4.69	0.21	5.62	2.08	2.50	<0.01	4.27						
STD SF-3T	Standard	4.11	0.06	0.017	4.70	0.20	5.54	2.09	2.50	<0.01	3.96						
STD SF-3T Expected		4.1	0.06	0.02074	4.67	0.19	5.43	2.06	2.47	0.00043	3.5						
STD R4T Expected		2.166	0.045	0.018	1.384		3.897	0.9	1.153	0.00016							
STD CDN-PGMS-14																	
STD CSC Expected																	
STD OREAS76A Expected																	
STD FA10R Expected																	
STD R3NI Expected													0.42				
STD SF-3A_NI Expected													0.3205				
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																

QUALITY CONTROL REPORT

SMI08000852.1

		WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
BLK	Blank					<0.02															
BLK	Blank					<0.02															
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank																				
BLK	Blank																				
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.001	<0.001	0.08	2.47	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank	<0.01	<2	<3	<2		<0.001	<0.001	<0.02	<0.01	4	<0.001	<0.001	0.08	2.50	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank					<0.02															

QUALITY CONTROL REPORT

SMI08000852.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
Prep Wash																	
G1	Prep Blank	2.59	0.09	0.001	0.70	0.25	7.48	2.58	2.96	<0.01	0.03	<0.001	<0.001	<0.001	0.05	0.02	N.A.
G1	Prep Blank	2.57	0.09	<0.001	0.70	0.26	7.42	2.61	2.97	<0.01	0.02	<0.001	<0.001	<0.001	0.05	0.02	N.A.
G1	Prep Blank																

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Email Distribution List
 Receiving Lab: Canada-Smithers
 Received: September 08, 2008
 Report Date: October 31, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000885.1

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-261B
 P.O. Number
 Number of Samples: 51

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	47	Crush split and pulverize drill core to 200 mesh		
3B	47	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	51	Analysis by Leco	0.1	Completed
7TD	51	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	51	Leached with H ₂ O ₂ + NH ₄ citrate	1	Completed
Specific Gravity	3	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.
 All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.
 "**" asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 31, 2008

Page: 2 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000885.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
647088	Drill Core	8.39	12	21	26	0.78	<0.001	0.025	<0.02	<0.01	<2	0.235	0.016	0.15	7.40	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647089	Drill Core	8.72	6	25	34	0.96	<0.001	0.033	<0.02	<0.01	<2	0.251	0.015	0.08	6.65	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647090A	Drill Core	9.07	14	35	49	1.78	<0.001	0.044	<0.02	<0.01	<2	0.388	0.026	0.12	9.60	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647090B	Client Dup		15	42	47	1.79	<0.001	0.043	<0.02	<0.01	<2	0.375	0.025	0.12	9.45	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647091	Drill Core	10.34	4	21	20	1.42	<0.001	0.025	<0.02	<0.01	<2	0.282	0.018	0.11	8.49	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647092	Drill Core	10.11	<2	11	26	0.79	<0.001	0.014	<0.02	<0.01	<2	0.264	0.014	0.12	7.83	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647093	Drill Core	9.24	<2	47	42	0.49	<0.001	0.027	<0.02	<0.01	<2	0.364	0.017	0.11	8.04	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647094	Drill Core	9.58	<2	10	9	0.17	<0.001	0.003	<0.02	<0.01	<2	0.259	0.015	0.11	7.49	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647095	Drill Core	8.96	<2	60	49	0.28	<0.001	0.018	<0.02	<0.01	<2	0.316	0.014	0.09	6.47	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647096	Drill Core	8.42	<2	32	21	0.15	<0.001	0.008	<0.02	<0.01	<2	0.240	0.014	0.09	5.75	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647097	Drill Core	8.86	<2	35	25	0.37	<0.001	0.042	<0.02	<0.01	<2	0.264	0.015	0.10	7.52	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647098	Drill Core	9.14	<2	33	32	1.10	<0.001	0.033	<0.02	<0.01	<2	0.283	0.015	0.12	8.53	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647099	Drill Core	9.58	<2	19	17	0.91	<0.001	0.028	<0.02	<0.01	<2	0.212	0.015	0.10	7.91	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647100	Rock Pulp	0.02	I.S.	I.S.	I.S.	1.38	<0.001	0.029	<0.02	<0.01	<2	0.252	0.016	0.11	8.68	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647101	Rock Pulp	0.02	I.S.	I.S.	I.S.	0.43	<0.001	0.053	<0.02	0.02	<2	0.232	0.011	0.11	9.02	<0.02	<0.01	<0.001	0.01	<0.01	0.02
647102	Drill Core	10.19	<2	15	18	2.07	<0.001	0.048	<0.02	<0.01	<2	0.354	0.023	0.11	9.73	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647103	Drill Core	10.05	5	19	27	2.92	<0.001	0.061	<0.02	<0.01	<2	0.394	0.025	0.10	10.37	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647104	Drill Core	9.95	<2	11	18	2.12	<0.001	0.046	<0.02	<0.01	<2	0.451	0.023	0.09	8.94	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647105	Drill Core	9.29	19	24	37	1.88	<0.001	0.051	<0.02	<0.01	<2	0.423	0.019	0.10	8.62	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647106	Drill Core	10.23	<2	15	18	1.29	<0.001	0.046	<0.02	<0.01	<2	0.296	0.017	0.10	8.65	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647107	Drill Core	9.99	6	18	20	0.78	<0.001	0.043	<0.02	<0.01	<2	0.301	0.014	0.10	7.82	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647108	Drill Core	8.99	5	38	41	0.62	<0.001	0.036	<0.02	<0.01	2	0.313	0.014	0.11	7.42	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647109	Drill Core	8.91	9	10	13	0.58	<0.001	0.033	<0.02	<0.01	<2	0.283	0.013	0.09	6.76	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647110	Drill Core	9.87	20	14	16	1.05	<0.001	0.045	<0.02	<0.01	<2	0.282	0.017	0.11	8.17	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647111	Drill Core	8.45	11	39	33	0.51	<0.001	0.034	<0.02	<0.01	<2	0.311	0.012	0.10	6.66	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647112	Drill Core	9.94	14	78	62	0.48	<0.001	0.027	<0.02	<0.01	<2	0.337	0.013	0.11	6.98	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647113	Drill Core	10.36	25	56	42	0.67	<0.001	0.027	<0.02	<0.01	<2	0.256	0.013	0.10	7.81	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647114	Drill Core	9.52	5	24	24	0.46	<0.001	0.018	<0.02	<0.01	2	0.220	0.012	0.10	6.96	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647115	Drill Core	8.68	<2	42	22	0.26	<0.001	0.015	<0.02	<0.01	<2	0.191	0.013	0.11	7.03	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647116	Drill Core	9.49	<2	51	21	0.11	<0.001	0.002	<0.02	<0.01	<2	0.274	0.011	0.09	5.30	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 31, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000885.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
647088	Drill Core	0.59	<0.01	0.119	22.79	<0.01	0.09	<0.01	<0.01	<0.01	0.79	0.021	0.212	0.014	0.78	2.12	N.A.
647089	Drill Core	2.01	0.02	0.072	17.61	0.08	1.05	<0.01	<0.01	<0.01	0.84	0.033	0.269	0.016	0.70	1.06	N.A.
647090A	Drill Core	0.53	<0.01	0.088	22.29	<0.01	0.06	<0.01	<0.01	<0.01	1.63	0.042	0.371	0.024	1.11	2.34	N.A.
647090B	Client Dup	0.52	<0.01	0.085	23.33	<0.01	0.05	<0.01	<0.01	<0.01	1.54	0.039	0.346	0.022	1.06	2.17	N.A.
647091	Drill Core	0.41	<0.01	0.130	24.96	<0.01	0.05	<0.01	<0.01	<0.01	1.23	0.023	0.229	0.012	0.96	1.85	N.A.
647092	Drill Core	0.68	<0.01	0.142	24.52	<0.01	0.05	<0.01	<0.01	<0.01	0.72	0.013	0.194	0.009	0.71	1.81	3.15
647093	Drill Core	0.70	<0.01	0.151	24.81	<0.01	0.05	<0.01	<0.01	<0.01	0.52	0.025	0.209	0.008	0.73	1.98	N.A.
647094	Drill Core	0.36	<0.01	0.204	25.21	<0.01	0.05	<0.01	<0.01	<0.01	0.18	0.003	0.090	0.006	0.50	2.40	N.A.
647095	Drill Core	0.45	<0.01	0.103	24.62	<0.01	0.04	<0.01	<0.01	<0.01	0.31	0.014	0.203	0.008	0.68	2.70	N.A.
647096	Drill Core	0.67	<0.01	0.125	25.19	<0.01	0.10	<0.01	<0.01	<0.01	0.17	0.006	0.113	0.008	0.63	3.01	N.A.
647097	Drill Core	0.44	<0.01	0.176	23.78	<0.01	0.04	<0.01	<0.01	<0.01	0.40	0.037	0.183	0.010	0.62	2.72	N.A.
647098	Drill Core	0.71	<0.01	0.129	22.94	<0.01	0.06	<0.01	<0.01	<0.01	0.98	0.030	0.263	0.012	0.85	2.17	N.A.
647099	Drill Core	0.60	<0.01	0.128	23.21	<0.01	0.16	<0.01	0.01	<0.01	0.85	0.023	0.174	0.011	0.73	1.81	N.A.
647100	Rock Pulp	0.69	<0.01	0.130	22.97	0.02	0.30	<0.01	0.07	<0.01	1.16	0.028	0.232	0.012	0.76	1.96	N.A.
647101	Rock Pulp	4.23	<0.01	1.081	13.56	0.18	4.10	0.32	0.11	<0.01	0.44	0.054	0.180	0.007	0.36	0.47	N.A.
647102	Drill Core	0.23	<0.01	0.085	24.24	<0.01	0.03	<0.01	<0.01	<0.01	1.67	0.043	0.328	0.018	1.00	2.03	N.A.
647103	Drill Core	0.61	<0.01	0.072	22.60	<0.01	0.04	<0.01	<0.01	<0.01	2.19	0.056	0.375	0.021	1.20	2.03	N.A.
647104	Drill Core	0.21	<0.01	0.136	24.85	<0.01	0.04	<0.01	<0.01	<0.01	1.66	0.043	0.449	0.020	1.19	2.06	N.A.
647105	Drill Core	0.26	<0.01	0.152	24.73	<0.01	0.04	<0.01	<0.01	<0.01	1.45	0.045	0.401	0.015	1.07	2.17	N.A.
647106	Drill Core	0.60	<0.01	0.127	23.29	0.01	0.35	<0.01	<0.01	<0.01	1.10	0.043	0.282	0.013	0.84	1.56	N.A.
647107	Drill Core	0.42	<0.01	0.136	24.28	<0.01	0.11	<0.01	<0.01	<0.01	0.74	0.036	0.269	0.010	0.74	2.29	N.A.
647108	Drill Core	0.53	<0.01	0.138	23.16	0.01	0.37	<0.01	<0.01	<0.01	0.61	0.030	0.276	0.009	0.75	1.73	N.A.
647109	Drill Core	0.71	<0.01	0.152	23.41	0.02	0.12	<0.01	<0.01	<0.01	0.61	0.030	0.249	0.009	0.67	1.51	N.A.
647110	Drill Core	0.34	<0.01	0.209	24.17	<0.01	0.05	<0.01	<0.01	<0.01	0.98	0.037	0.237	0.012	0.82	2.47	N.A.
647111	Drill Core	0.66	0.01	0.154	22.42	0.03	0.50	<0.01	0.09	<0.01	0.55	0.027	0.259	0.009	0.69	2.38	N.A.
647112	Drill Core	0.45	<0.01	0.646	24.50	0.01	0.10	<0.01	<0.01	<0.01	0.53	0.022	0.243	0.007	0.75	2.28	2.89
647113	Drill Core	0.12	<0.01	0.197	24.53	<0.01	0.05	<0.01	<0.01	<0.01	0.68	0.020	0.199	0.008	0.66	2.13	N.A.
647114	Drill Core	0.40	<0.01	0.177	23.46	<0.01	0.18	<0.01	<0.01	<0.01	0.50	0.015	0.178	0.009	0.57	2.18	N.A.
647115	Drill Core	1.89	0.02	0.156	20.63	0.05	1.58	<0.01	0.21	<0.01	0.28	0.012	0.154	0.010	0.34	0.81	N.A.
647116	Drill Core	0.26	<0.01	0.156	25.01	<0.01	0.15	<0.01	<0.01	<0.01	0.16	0.002	0.132	0.006	0.43	2.61	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 31, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000885.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
647117	Drill Core	8.92	6	29	31	0.11	<0.001	0.002	<0.02	<0.01	<2	0.262	0.010	0.09	5.18	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647118	Drill Core	9.48	<2	51	40	0.13	<0.001	0.002	<0.02	<0.01	<2	0.267	0.010	0.09	5.48	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647119	Drill Core	9.04	<2	31	28	3.52	0.003	0.042	<0.02	<0.01	3	0.318	0.021	0.13	11.57	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
647120A	Drill Core	2.90	7	45	56	10.28	0.003	0.124	<0.02	<0.01	2	0.546	0.041	0.14	20.38	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
647120B	Client Dup		5	55	63	11.15	0.004	0.149	<0.02	<0.01	3	0.630	0.047	0.12	21.99	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
647121	Drill Core	7.71	4	25	25	1.51	<0.001	0.030	<0.02	<0.01	2	0.184	0.015	0.14	8.88	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
647122	Drill Core	9.11	<2	6	7	0.63	<0.001	0.012	<0.02	<0.01	<2	0.165	0.011	0.10	7.15	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647123	Drill Core	9.07	9	12	12	0.84	<0.001	0.012	<0.02	<0.01	<2	0.209	0.013	0.11	8.07	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647124	Drill Core	10.69	11	14	17	4.21	0.004	0.076	<0.02	<0.01	<2	0.268	0.019	0.12	11.89	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
647125	Rock Pulp	0.02	I.S.	I.S.	I.S.	4.12	0.001	0.047	<0.02	<0.01	2	0.403	0.027	0.12	12.52	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647126	Rock Pulp	0.02	I.S.	I.S.	I.S.	0.40	<0.001	0.053	<0.02	0.02	<2	0.228	0.011	0.11	8.98	<0.02	<0.01	<0.001	0.01	<0.01	0.02
647127	Drill Core	9.99	<2	8	9	3.11	0.002	0.034	<0.02	<0.01	<2	0.203	0.016	0.12	11.08	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
647128	Drill Core	9.58	<2	9	8	2.03	0.001	0.030	<0.02	<0.01	<2	0.158	0.013	0.14	10.03	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
647129	Drill Core	6.12	<2	71	17	3.35	0.003	0.031	<0.02	<0.01	<2	0.153	0.013	0.12	9.27	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
647130	Drill Core	2.02	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.002	<0.001	0.07	1.08	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
647131	Drill Core	4.21	3	4	9	2.02	<0.001	0.020	<0.02	<0.01	<2	0.127	0.013	0.13	10.62	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
647132	Drill Core	10.09	2	6	11	1.30	<0.001	0.013	<0.02	<0.01	<2	0.192	0.014	0.13	9.54	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
647133	Drill Core	10.81	<2	8	11	1.81	<0.001	0.022	<0.02	<0.01	<2	0.162	0.020	0.12	10.23	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647134	Drill Core	10.19	3	14	20	2.41	<0.001	0.032	<0.02	<0.01	<2	0.296	0.025	0.11	11.33	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647135	Drill Core	10.27	7	17	28	1.67	<0.001	0.032	<0.02	<0.01	<2	0.365	0.021	0.12	9.94	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647136	Drill Core	10.51	10	26	41	1.49	<0.001	0.034	<0.02	<0.01	<2	0.461	0.018	0.11	9.07	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 31, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000885.1

Method		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
Unit		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
MDL		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
647117	Drill Core	0.23	<0.01	0.160	24.13	<0.01	0.06	<0.01	<0.01	<0.01	0.18	0.001	0.157	0.006	0.43	3.32	N.A.
647118	Drill Core	1.56	<0.01	0.144	23.87	0.03	0.69	<0.01	<0.01	<0.01	0.19	0.002	0.150	0.006	0.46	2.29	N.A.
647119	Drill Core	2.35	<0.01	0.125	16.49	0.03	0.23	0.06	0.03	<0.01	2.93	0.039	0.313	0.020	1.23	1.13	N.A.
647120A	Drill Core	3.27	<0.01	0.123	12.82	0.02	0.11	0.06	0.01	<0.01	7.16	0.118	0.544	0.038	1.00	0.18	N.A.
647120B	Client Dup	3.22	<0.01	0.127	12.55	0.02	0.10	0.06	<0.01	<0.01	7.86	0.148	0.653	0.045	1.08	0.16	N.A.
647121	Drill Core	1.94	<0.01	0.159	19.45	0.04	0.48	0.03	0.16	<0.01	1.42	0.029	0.162	0.012	0.56	0.83	N.A.
647122	Drill Core	1.17	<0.01	0.108	20.27	0.02	0.15	0.02	0.01	<0.01	0.55	0.011	0.148	0.009	0.32	0.45	N.A.
647123	Drill Core	1.03	<0.01	0.152	22.11	0.02	0.10	<0.01	<0.01	<0.01	0.77	0.011	0.171	0.009	0.43	0.75	N.A.
647124	Drill Core	2.00	<0.01	0.106	16.85	0.03	0.22	0.07	0.08	<0.01	3.35	0.075	0.253	0.017	0.58	0.30	N.A.
647125	Rock Pulp	1.12	<0.01	0.143	20.98	0.02	0.28	0.03	0.09	<0.01	3.39	0.047	0.414	0.024	1.06	1.40	N.A.
647126	Rock Pulp	4.20	<0.01	1.059	13.37	0.18	4.05	0.31	0.11	<0.01	0.45	0.054	0.184	0.007	0.28	0.21	N.A.
647127	Drill Core	1.68	<0.01	0.125	16.70	0.03	0.23	0.07	0.06	<0.01	2.81	0.033	0.189	0.014	0.48	0.29	N.A.
647128	Drill Core	2.24	<0.01	0.138	16.27	0.04	0.24	0.08	0.06	<0.01	1.73	0.029	0.146	0.010	0.41	0.25	N.A.
647129	Drill Core	8.23	<0.01	0.184	14.35	0.04	0.22	0.04	<0.01	<0.01	3.04	0.031	0.145	0.012	0.61	0.35	N.A.
647130	Drill Core	1.84	0.02	<0.001	0.26	0.07	6.62	3.66	1.33	<0.01	0.03	<0.001	0.001	<0.001	0.03	0.02	N.A.
647131	Drill Core	3.35	<0.01	0.156	20.03	0.02	0.14	0.03	0.01	<0.01	1.69	0.018	0.110	0.010	0.48	0.96	N.A.
647132	Drill Core	2.62	<0.01	0.135	22.84	0.02	0.14	0.03	<0.01	<0.01	1.23	0.012	0.155	0.009	0.72	1.63	3.29
647133	Drill Core	1.34	<0.01	0.230	23.25	0.02	0.15	0.01	<0.01	<0.01	1.52	0.021	0.147	0.015	0.60	1.45	N.A.
647134	Drill Core	0.54	<0.01	0.152	23.35	0.01	0.08	<0.01	<0.01	<0.01	2.11	0.030	0.273	0.021	0.97	2.55	N.A.
647135	Drill Core	0.92	<0.01	0.083	23.63	0.02	0.12	<0.01	<0.01	<0.01	1.46	0.031	0.327	0.015	0.95	1.97	N.A.
647136	Drill Core	0.08	<0.01	0.074	24.57	<0.01	0.02	<0.01	<0.01	<0.01	1.36	0.033	0.415	0.014	1.04	2.62	N.A.

QUALITY CONTROL REPORT

SMI08000885.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
Pulp Duplicates																				
REP G1	QC					<0.001	<0.001	<0.02	<0.01	<2	0.002	<0.001	0.08	2.16	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
647091	Drill Core	10.34	4	21	20	1.42	<0.001	0.025	<0.02	<0.01	<2	0.282	0.018	0.11	8.49	<0.02	<0.01	<0.001	<0.01	<0.01
REP 647091	QC					1.39														
647098	Drill Core	9.14	<2	33	32	1.10	<0.001	0.033	<0.02	<0.01	<2	0.283	0.015	0.12	8.53	<0.02	<0.01	<0.001	<0.01	<0.01
REP 647098	QC					<0.001	0.033	<0.02	<0.01	<2	0.282	0.015	0.12	8.47	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647111	Drill Core	8.45	11	39	33	0.51	<0.001	0.034	<0.02	<0.01	<2	0.311	0.012	0.10	6.66	<0.02	<0.01	<0.001	<0.01	<0.01
REP 647111	QC																			
647113	Drill Core	10.36	25	56	42	0.67	<0.001	0.027	<0.02	<0.01	<2	0.256	0.013	0.10	7.81	<0.02	<0.01	<0.001	<0.01	<0.01
REP 647113	QC		16	50	36															
647114	Drill Core	9.52	5	24	24	0.46	<0.001	0.018	<0.02	<0.01	2	0.220	0.012	0.10	6.96	<0.02	<0.01	<0.001	<0.01	<0.01
REP 647114	QC					0.47														
647125	Rock Pulp	0.02	I.S.	I.S.	I.S.	4.12	0.001	0.047	<0.02	<0.01	2	0.403	0.027	0.12	12.52	<0.02	<0.01	<0.001	<0.01	<0.01
REP 647125	QC																			
Core Reject Duplicates																				
647095	Drill Core	8.96	<2	60	49	0.28	<0.001	0.018	<0.02	<0.01	<2	0.316	0.014	0.09	6.47	<0.02	<0.01	<0.001	<0.01	<0.01
DUP 647095	QC		<2	67	48	0.29	<0.001	0.017	<0.02	<0.01	<2	0.316	0.014	0.09	6.32	<0.02	<0.01	<0.001	<0.01	<0.01
647129	Drill Core	6.12	<2	71	17	3.35	0.003	0.031	<0.02	<0.01	<2	0.153	0.013	0.12	9.27	<0.02	<0.01	<0.001	<0.01	<0.01
DUP 647129	QC		<2	<3	9	3.32	0.003	0.030	<0.02	<0.01	<2	0.147	0.013	0.12	8.94	<0.02	<0.01	<0.001	<0.01	<0.01
Reference Materials																				
STD CDN-PGMS-8	Standard		858	429	1432															
STD CDN-PGMS-8	Standard		755	439	1412															
STD CDN-PGMS-14	Standard		269	109	453															
STD CDN-PGMS-8	Standard		867	426	1575															
STD CSC	Standard					4.38														
STD CSC	Standard					4.06														
STD FA10R	Standard		481	467	496															
STD FA10R	Standard		489	465	500															

QUALITY CONTROL REPORT

SMI08000885.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG	
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%		
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
Pulp Duplicates																	
REP G1	QC										<0.001	<0.001	<0.001	0.06	0.02		
REP G1	QC	2.49	0.08	0.003	0.79	0.26	7.07	2.57	2.96	<0.01	<0.01						
647091	Drill Core	0.41	<0.01	0.130	24.96	<0.01	0.05	<0.01	<0.01	<0.01	1.23	0.023	0.229	0.012	0.96	1.85	N.A.
REP 647091	QC																
647098	Drill Core	0.71	<0.01	0.129	22.94	<0.01	0.06	<0.01	<0.01	<0.01	0.98	0.030	0.263	0.012	0.85	2.17	N.A.
REP 647098	QC	0.71	<0.01	0.135	22.48	<0.01	0.06	<0.01	<0.01	<0.01	0.97						
647111	Drill Core	0.66	0.01	0.154	22.42	0.03	0.50	<0.01	0.09	<0.01	0.55	0.027	0.259	0.009	0.69	2.38	N.A.
REP 647111	QC										0.027	0.259	0.009	0.69	2.38		
647113	Drill Core	0.12	<0.01	0.197	24.53	<0.01	0.05	<0.01	<0.01	<0.01	0.68	0.020	0.199	0.008	0.66	2.13	N.A.
REP 647113	QC																
647114	Drill Core	0.40	<0.01	0.177	23.46	<0.01	0.18	<0.01	<0.01	<0.01	0.50	0.015	0.178	0.009	0.57	2.18	N.A.
REP 647114	QC																
647125	Rock Pulp	1.12	<0.01	0.143	20.98	0.02	0.28	0.03	0.09	<0.01	3.39	0.047	0.414	0.024	1.06	1.40	N.A.
REP 647125	QC										0.047	0.406	0.023	1.05	1.38		
Core Reject Duplicates																	
647095	Drill Core	0.45	<0.01	0.103	24.62	<0.01	0.04	<0.01	<0.01	<0.01	0.31	0.014	0.203	0.008	0.68	2.70	N.A.
DUP 647095	QC	0.46	<0.01	0.109	25.14	<0.01	0.04	<0.01	<0.01	<0.01	0.30	0.013	0.174	0.008	0.62	2.44	N.A.
647129	Drill Core	8.23	<0.01	0.184	14.35	0.04	0.22	0.04	<0.01	<0.01	3.04	0.031	0.145	0.012	0.61	0.35	N.A.
DUP 647129	QC	8.32	<0.01	0.175	14.36	0.04	0.22	0.04	<0.01	<0.01	2.78	0.029	0.136	0.011	0.51	0.28	N.A.
Reference Materials																	
STD CDN-PGMS-8	Standard																
STD CDN-PGMS-8	Standard																
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-8	Standard																
STD CSC	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD FA10R	Standard																

QUALITY CONTROL REPORT

SMI08000885.1

		WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
STD FA10R	Standard		451	452	458																
STD FA10R	Standard		508	469	503																
STD OREAS76A	Standard					18.12															
STD OREAS76A	Standard					17.59															
STD R4T	Standard						0.063	0.512	1.56	3.52	91	0.350	0.039	0.09	24.68	<0.02	0.02	0.018	0.02	<0.01	0.02
STD R4T	Standard						0.061	0.508	1.54	3.39	86	0.355	0.040	0.09	24.19	<0.02	0.02	0.018	0.01	<0.01	0.02
STD R4T	Standard						0.061	0.500	1.53	3.37	86	0.353	0.040	0.09	23.99	<0.02	0.02	0.018	0.01	<0.01	0.02
STD SF-3A_NI	Standard																				
STD SF-3A_NI	Standard																				
STD SF-3A_NI	Standard																				
STD SF-3T	Standard						0.032	0.770	0.95	1.09	53	0.346	0.018	0.42	8.02	<0.02	0.04	0.004	<0.01	<0.01	0.01
STD SF-3T	Standard						0.032	0.756	0.94	1.06	51	0.344	0.016	0.42	8.26	<0.02	0.04	0.004	<0.01	<0.01	0.01
STD SF-3T	Standard						0.031	0.765	0.94	1.07	52	0.348	0.018	0.43	8.34	<0.02	0.04	0.004	<0.01	<0.01	0.01
STD SF-3T Expected							0.032	0.7723	0.961	1.0672	52	0.35	0.0181	0.432	8.33	0.004	0.044	0.00475	0.00111	0.00048	0.0143
STD R4T Expected							0.062	0.502	1.518	3.376	86	0.348	0.039	0.086	24.07	0.0087	0.0185	0.018	0.0138	0.0018	0.016
STD CDN-PGMS-14			259	119	451																
STD FA10R Expected			485	472	476																
STD CDN-PGMS-8 Expected			820	440	1500																
STD CSC Expected						4.25															
STD OREAS76A Expected						18															
STD SF-3A_NI Expected																					
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank						<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
BLK	Blank						<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
BLK	Blank						<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
BLK	Blank		<2	<3	<2																

QUALITY CONTROL REPORT

SMI08000885.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																
STD OREAS76A	Standard																
STD R4T	Standard	2.13	0.04	0.018	1.42	0.20	3.93	0.90	1.15	<0.01	13.44						
STD R4T	Standard	2.16	0.04	0.018	1.43	0.19	3.95	0.90	1.18	<0.01	12.42						
STD R4T	Standard	2.12	0.05	0.017	1.41	0.19	3.92	0.91	1.16	<0.01	12.63						
STD SF-3A_NI	Standard											0.778	0.318	0.015	1.42	1.87	
STD SF-3A_NI	Standard											0.787	0.313	0.015	1.52	2.02	
STD SF-3A_NI	Standard											0.754	0.332	0.016	1.77	2.73	
STD SF-3T	Standard	4.01	0.05	0.020	4.56	0.20	5.49	2.08	2.44	<0.01	4.29						
STD SF-3T	Standard	3.98	0.05	0.015	4.51	0.19	5.38	2.08	2.47	<0.01	4.17						
STD SF-3T	Standard	4.02	0.06	0.016	4.56	0.19	5.41	2.08	2.46	<0.01	4.35						
STD SF-3T Expected		4.1	0.06	0.02074	4.67	0.19	5.43	2.06	2.47	0.00043	3.5						
STD R4T Expected		2.166	0.045	0.018	1.384		3.897	0.9	1.153	0.00016							
STD CDN-PGMS-14																	
STD FA10R Expected																	
STD CDN-PGMS-8 Expected																	
STD CSC Expected																	
STD OREAS76A Expected																	
STD SF-3A_NI Expected												0.3205					
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																

QUALITY CONTROL REPORT

SMI08000885.1

		WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank					<0.02															
BLK	Blank					<0.02															
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2	0.03	<0.001	<0.001	<0.02	<0.01	<2	0.001	<0.001	0.07	2.27	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank	<0.01	<2	<3	<2	<0.02															
G1	Prep Blank																				
G1	Prep Blank						<0.001	<0.001	<0.02	<0.01	<2	0.002	<0.001	0.07	2.18	<0.02	0.07	<0.001	<0.01	<0.01	<0.01

QUALITY CONTROL REPORT

SMI08000885.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NIS	8NIS	8NIS	8NIS	8NIS	G8SG	
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%		
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
BLK	Blank																	
BLK	Blank																	
BLK	Blank																	
BLK	Blank																	
BLK	Blank																	
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01		
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01		
Prep Wash																		
G1	Prep Blank	2.45	0.08	0.002	0.72	0.25	6.52	2.55	2.92	<0.01	0.02						N.A.	
G1	Prep Blank											<0.001	<0.001	<0.001	0.04	0.02		N.A.
G1	Prep Blank											<0.001	<0.001	<0.001	0.04	0.02		
G1	Prep Blank	2.46	0.07	0.002	0.76	0.25	6.82	2.55	2.83	<0.01	<0.01							



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Email Distribution List
 Receiving Lab: Canada-Smithers
 Received: September 08, 2008
 Report Date: October 30, 2008
 Page: 1 of 2

CERTIFICATE OF ANALYSIS

SMI08000891.1

CLIENT JOB INFORMATION

Project: Turnagain Ni
 Shipment ID: C08-261C
 P.O. Number
 Number of Samples: 22

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	20	Crush split and pulverize drill core to 200 mesh		
3B	22	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	22	Analysis by Leco	0.1	Completed
7TD	22	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	22	Leached with H2O2 + NH4 citrate	1	Completed
Specific Gravity	1	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.
 All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.
 "**" asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain Ni
 Report Date: October 30, 2008

Page: 2 of 2 Part 1

CERTIFICATE OF ANALYSIS

SMI08000891.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
647137	Drill Core	10.11	25	29	42	1.67	<0.001	0.036	<0.02	<0.01	<2	0.475	0.020	0.11	8.85	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647138	Drill Core	10.67	5	15	23	1.07	<0.001	0.037	<0.02	<0.01	<2	0.329	0.016	0.11	8.16	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647139	Drill Core	10.51	3	17	23	0.81	<0.001	0.027	<0.02	<0.01	<2	0.254	0.015	0.12	7.51	<0.02	0.02	<0.001	<0.01	<0.01	<0.01
647140	Drill Core	9.71	8	21	33	0.55	<0.001	0.028	<0.02	<0.01	<2	0.292	0.015	0.12	7.33	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647141	Drill Core	10.71	18	26	30	0.49	<0.001	0.052	<0.02	<0.01	<2	0.266	0.014	0.12	7.80	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647142	Drill Core	10.88	14	23	34	1.98	<0.001	0.039	<0.02	<0.01	<2	0.363	0.021	0.12	9.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647143	Drill Core	10.27	21	28	32	1.28	<0.001	0.027	<0.02	<0.01	<2	0.352	0.018	0.12	8.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647144	Drill Core	10.45	6	54	74	2.63	<0.001	0.052	<0.02	<0.01	<2	0.557	0.025	0.11	10.55	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647145	Drill Core	10.22	6	26	39	2.30	<0.001	0.057	<0.02	<0.01	<2	0.406	0.022	0.11	10.24	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647146	Drill Core	9.87	5	34	37	2.50	<0.001	0.053	<0.02	<0.01	<2	0.325	0.023	0.12	10.56	<0.02	0.01	<0.001	<0.01	<0.01	<0.01
647147	Drill Core	10.53	6	26	36	2.42	<0.001	0.063	<0.02	<0.01	<2	0.322	0.022	0.11	10.66	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647148	Drill Core	10.74	6	39	49	2.56	<0.001	0.071	<0.02	<0.01	<2	0.372	0.021	0.12	10.63	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647149	Drill Core	10.67	8	35	34	2.25	<0.001	0.052	<0.02	<0.01	<2	0.299	0.021	0.12	11.32	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647150	Rock Pulp	0.02	I.S.	I.S.	I.S.	1.42	<0.001	0.029	<0.02	<0.01	<2	0.256	0.016	0.11	8.69	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647151	Rock Pulp	0.02	I.S.	I.S.	I.S.	0.49	<0.001	0.053	<0.02	0.02	<2	0.234	0.011	0.11	9.07	<0.02	<0.01	<0.001	0.01	<0.01	0.02
647152	Drill Core	10.73	13	8	12	2.65	<0.001	0.037	<0.02	<0.01	<2	0.209	0.023	0.12	11.06	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647153	Drill Core	10.64	3	18	17	1.99	<0.001	0.034	<0.02	<0.01	<2	0.195	0.020	0.13	10.14	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647154	Drill Core	10.77	3	18	21	0.77	<0.001	0.019	<0.02	<0.01	<2	0.211	0.016	0.12	8.26	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647155	Drill Core	10.21	19	31	33	0.53	<0.001	0.028	<0.02	<0.01	<2	0.244	0.014	0.13	7.89	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647156	Drill Core	9.93	43	20	41	0.63	<0.001	0.034	<0.02	<0.01	<2	0.254	0.014	0.12	7.98	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647157	Drill Core	10.64	5	10	11	1.57	<0.001	0.036	<0.02	<0.01	<2	0.227	0.020	0.12	9.84	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647158	Drill Core	8.04	<2	9	21	1.88	<0.001	0.039	<0.02	<0.01	<2	0.186	0.022	0.14	10.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain Ni
 Report Date: October 30, 2008

Page: 2 of 2 Part 2

CERTIFICATE OF ANALYSIS

SMI08000891.1

Method		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
Unit		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
MDL		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
647137	Drill Core	0.29	<0.01	0.110	23.95	<0.01	0.05	<0.01	<0.01	<0.01	1.40	0.034	0.417	0.014	1.07	2.22	N.A.
647138	Drill Core	0.68	<0.01	0.212	24.52	0.04	0.22	<0.01	<0.01	<0.01	0.89	0.038	0.277	0.011	0.82	1.97	N.A.
647139	Drill Core	1.20	0.02	0.191	21.00	0.04	1.43	0.61	0.28	<0.01	0.71	0.028	0.206	0.010	0.68	1.71	N.A.
647140	Drill Core	0.18	<0.01	0.186	25.23	<0.01	0.07	<0.01	<0.01	<0.01	0.50	0.028	0.179	0.008	0.73	2.37	N.A.
647141	Drill Core	0.26	<0.01	0.215	25.37	0.01	0.09	<0.01	<0.01	<0.01	0.46	0.049	0.156	0.007	0.72	2.47	N.A.
647142	Drill Core	0.29	<0.01	0.230	25.90	0.01	0.10	<0.01	<0.01	<0.01	1.60	0.039	0.324	0.016	0.97	2.12	N.A.
647143	Drill Core	0.08	<0.01	0.147	25.66	<0.01	0.05	<0.01	<0.01	<0.01	0.97	0.027	0.303	0.012	0.81	1.91	N.A.
647144	Drill Core	0.37	<0.01	0.141	24.22	<0.01	0.06	<0.01	<0.01	<0.01	2.19	0.053	0.516	0.020	1.23	2.14	N.A.
647145	Drill Core	0.17	<0.01	0.112	24.52	<0.01	0.07	<0.01	<0.01	<0.01	1.82	0.059	0.370	0.018	1.04	2.31	N.A.
647146	Drill Core	0.44	<0.01	0.204	23.06	0.02	0.32	0.01	0.06	<0.01	2.02	0.053	0.310	0.019	1.01	1.90	N.A.
647147	Drill Core	0.43	<0.01	0.228	23.47	<0.01	0.11	<0.01	<0.01	<0.01	1.92	0.066	0.295	0.018	0.99	2.01	N.A.
647148	Drill Core	0.64	<0.01	0.181	23.82	<0.01	0.09	<0.01	<0.01	<0.01	2.07	0.071	0.341	0.017	1.12	2.09	N.A.
647149	Drill Core	0.53	<0.01	0.239	23.79	0.02	0.14	<0.01	<0.01	<0.01	1.76	0.049	0.269	0.016	0.95	1.89	N.A.
647150	Rock Pulp	0.71	<0.01	0.128	23.40	0.02	0.31	<0.01	0.07	<0.01	1.20	0.029	0.215	0.012	0.84	2.51	N.A.
647151	Rock Pulp	4.31	<0.01	0.985	13.32	0.18	4.08	0.33	0.11	<0.01	0.45	0.055	0.184	0.007	0.44	0.52	N.A.
647152	Drill Core	0.37	<0.01	0.160	23.81	<0.01	0.06	<0.01	<0.01	<0.01	2.01	0.039	0.199	0.019	0.94	2.34	3.17
647153	Drill Core	0.34	<0.01	0.234	24.52	<0.01	0.06	<0.01	<0.01	<0.01	1.54	0.034	0.165	0.014	0.83	2.02	N.A.
647154	Drill Core	0.19	<0.01	0.212	25.50	<0.01	0.08	<0.01	<0.01	<0.01	0.62	0.018	0.142	0.008	0.68	2.14	N.A.
647155	Drill Core	0.28	<0.01	0.387	24.97	<0.01	0.09	<0.01	<0.01	<0.01	0.49	0.027	0.143	0.006	0.81	2.53	N.A.
647156	Drill Core	0.37	<0.01	0.204	24.59	0.01	0.14	<0.01	0.01	<0.01	0.53	0.035	0.152	0.007	0.77	2.25	N.A.
647157	Drill Core	0.48	<0.01	0.191	23.60	0.02	0.22	<0.01	0.02	<0.01	1.24	0.036	0.186	0.013	0.81	2.10	N.A.
647158	Drill Core	0.68	<0.01	0.157	24.21	<0.01	0.06	<0.01	<0.01	<0.01	1.55	0.040	0.151	0.016	0.82	1.92	N.A.

QUALITY CONTROL REPORT

SMI08000891.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
Pulp Duplicates																					
647139	Drill Core	10.51	3	17	23	0.81	<0.001	0.027	<0.02	<0.01	<2	0.254	0.015	0.12	7.51	<0.02	0.02	<0.001	<0.01	<0.01	<0.01
REP 647139	QC																				
647147	Drill Core	10.53	6	26	36	2.42	<0.001	0.063	<0.02	<0.01	<2	0.322	0.022	0.11	10.66	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 647147	QC		7	26	37																
647155	Drill Core	10.21	19	31	33	0.53	<0.001	0.028	<0.02	<0.01	<2	0.244	0.014	0.13	7.89	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 647155	QC					0.53															
647156	Drill Core	9.93	43	20	41	0.63	<0.001	0.034	<0.02	<0.01	<2	0.254	0.014	0.12	7.98	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 647156	QC		36	25	35																
647158	Drill Core	8.04	<2	9	21	1.88	<0.001	0.039	<0.02	<0.01	<2	0.186	0.022	0.14	10.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 647158	QC					<0.001	0.039	<0.02	<0.01	<2	0.185	0.023	0.14	10.86	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
Core Reject Duplicates																					
647152	Drill Core	10.73	13	8	12	2.65	<0.001	0.037	<0.02	<0.01	<2	0.209	0.023	0.12	11.06	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
DUP 647152	QC		10	11	11	2.53	<0.001	0.039	<0.02	<0.01	<2	0.207	0.025	0.12	11.41	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
Reference Materials																					
STD CDN-PGMS-8	Standard		755	439	1412																
STD CDN-PGMS-8	Standard		680	404	1411																
STD CDN-PGMS-8	Standard		867	426	1575																
STD CSC	Standard					4.31															
STD FA10R	Standard		489	465	500																
STD FA10R	Standard		474	475	485																
STD FA10R	Standard		508	469	503																
STD OREAS76A	Standard					17.99															
STD R4T	Standard					0.061	0.500	1.53	3.37	86	0.353	0.040	0.09	23.99	<0.02	0.02	0.018	0.01	<0.01	0.02	
STD SF-3A_NI	Standard																				
STD SF-3T	Standard					0.031	0.765	0.94	1.07	52	0.348	0.018	0.43	8.34	<0.02	0.04	0.004	<0.01	<0.01	0.01	
STD SF-3T Expected						0.032	0.7723	0.961	1.0672	52	0.35	0.0181	0.432	8.33	0.004	0.044	0.00475	0.00111	0.00048	0.0143	
STD R4T Expected						0.062	0.502	1.518	3.376	86	0.348	0.039	0.086	24.07	0.0087	0.0185	0.018	0.0138	0.0018	0.016	
STD FA10R Expected			485	472	476																

QUALITY CONTROL REPORT

SMI08000891.1

Method		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
Unit		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
Pulp Duplicates																	
647139	Drill Core	1.20	0.02	0.191	21.00	0.04	1.43	0.61	0.28	<0.01	0.71	0.028	0.206	0.010	0.68	1.71	N.A.
REP 647139	QC											0.028	0.204	0.010	0.68	1.75	
647147	Drill Core	0.43	<0.01	0.228	23.47	<0.01	0.11	<0.01	<0.01	<0.01	1.92	0.066	0.295	0.018	0.99	2.01	N.A.
REP 647147	QC																
647155	Drill Core	0.28	<0.01	0.387	24.97	<0.01	0.09	<0.01	<0.01	<0.01	0.49	0.027	0.143	0.006	0.81	2.53	N.A.
REP 647155	QC																
647156	Drill Core	0.37	<0.01	0.204	24.59	0.01	0.14	<0.01	0.01	<0.01	0.53	0.035	0.152	0.007	0.77	2.25	N.A.
REP 647156	QC											0.034	0.151	0.007	0.76	2.18	
647158	Drill Core	0.68	<0.01	0.157	24.21	<0.01	0.06	<0.01	<0.01	<0.01	1.55	0.040	0.151	0.016	0.82	1.92	N.A.
REP 647158	QC	0.68	<0.01	0.160	24.48	<0.01	0.06	<0.01	<0.01	<0.01	1.47						
Core Reject Duplicates																	
647152	Drill Core	0.37	<0.01	0.160	23.81	<0.01	0.06	<0.01	<0.01	<0.01	2.01	0.039	0.199	0.019	0.94	2.34	3.17
DUP 647152	QC	0.29	<0.01	0.163	24.39	<0.01	0.06	<0.01	<0.01	<0.01	1.99	0.038	0.184	0.019	0.78	1.90	N.A.
Reference Materials																	
STD CDN-PGMS-8	Standard																
STD CDN-PGMS-8	Standard																
STD CDN-PGMS-8	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																
STD R4T	Standard	2.12	0.05	0.017	1.41	0.19	3.92	0.91	1.16	<0.01	12.63						
STD SF-3A_NI	Standard											0.754	0.332	0.016	1.77	2.73	
STD SF-3T	Standard	4.02	0.06	0.016	4.56	0.19	5.41	2.08	2.46	<0.01	4.35						
STD SF-3T Expected		4.1	0.06	0.02074	4.67	0.19	5.43	2.06	2.47	0.00043	3.5						
STD R4T Expected		2.166	0.045	0.018	1.384		3.897	0.9	1.153	0.00016							
STD FA10R Expected																	

QUALITY CONTROL REPORT

SMI08000891.1

		WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
STD CDN-PGMS-8 Expected			820	440	1500																
STD CSC Expected						4.25															
STD OREAS76A Expected						18															
STD SF-3A_NI Expected																					
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank					<0.02															
BLK	Blank																				
Prep Wash																					
G1	Prep Blank	<0.01	13	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.34	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank	<0.01	2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.001	<0.001	0.07	2.36	<0.02	0.07	<0.001	<0.01	<0.01	<0.01

QUALITY CONTROL REPORT

SMI08000891.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG				
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0
STD CDN-PGMS-8 Expected																					
STD CSC Expected																					
STD OREAS76A Expected																					
STD SF-3A_NI Expected													0.3205								
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
Prep Wash																					
G1	Prep Blank	2.42	0.08	0.001	0.70	0.24	7.16	2.59	2.98	<0.01	<0.01	<0.001	<0.001	<0.001	0.05	0.02	N.A.				
G1	Prep Blank	2.36	0.08	0.001	0.70	0.22	7.09	2.53	3.02	<0.01	<0.01	<0.001	<0.001	<0.001	0.03	0.02	N.A.				

Hole 08-262

Hole 08-263

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Email Distribution List
 Receiving Lab: Canada-Smithers
 Received: September 08, 2008
 Report Date: November 06, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000880.1

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-263A
 P.O. Number
 Number of Samples: 42

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	40	Crush split and pulverize drill core to 200 mesh		
3B	42	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	42	Analysis by Leco	0.1	Completed
7TD	42	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	42	Leached with H2O2 + NH4 citrate	1	Completed
Specific Gravity	3	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. ** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

ACME ANALYTICAL LABORATORIES LTD.

www.acmelab.com

Client:

Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
Vancouver BC V6E 3V7 Canada

Project:

Turnagain

Report Date:

November 06, 2008

Page:

2 of 3

Part 1

CERTIFICATE OF ANALYSIS

SMI08000880.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
358706	Drill Core	1.41	<2	<3	4	1.28	<0.001	0.020	<0.02	<0.01	<2	0.082	0.009	0.10	6.80	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
358707	Drill Core	6.74	<2	5	10	1.05	<0.001	0.015	<0.02	<0.01	<2	0.173	0.012	0.15	9.77	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
358708	Drill Core	8.95	<2	5	4	1.27	<0.001	0.024	<0.02	<0.01	<2	0.131	0.015	0.13	9.23	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
358709	Drill Core	8.35	<2	<3	<2	0.83	<0.001	0.016	<0.02	<0.01	<2	0.158	0.015	0.13	8.75	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
358710	Drill Core	8.60	<2	<3	3	0.49	<0.001	0.024	<0.02	<0.01	<2	0.176	0.013	0.13	8.00	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
358711	Drill Core	7.22	<2	10	15	0.50	<0.001	0.018	<0.02	<0.01	<2	0.204	0.012	0.14	8.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
358712	Drill Core	7.48	<2	<3	4	1.09	<0.001	0.015	<0.02	<0.01	<2	0.124	0.011	0.12	8.39	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
358713	Drill Core	7.41	<2	<3	3	1.08	<0.001	0.010	<0.02	<0.01	<2	0.103	0.009	0.14	7.94	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
358714	Drill Core	8.23	<2	<3	3	1.81	<0.001	0.011	<0.02	<0.01	<2	0.087	0.010	0.15	8.67	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358715	Drill Core	7.59	<2	<3	14	0.98	<0.001	0.006	<0.02	<0.01	<2	0.107	0.008	0.16	7.79	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358716	Drill Core	7.59	4	<3	13	0.79	<0.001	0.004	<0.02	<0.01	<2	0.140	0.008	0.14	8.11	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
358717	Drill Core	8.09	<2	8	3	2.05	<0.001	0.009	<0.02	<0.01	<2	0.132	0.010	0.16	9.14	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358718	Drill Core	8.19	<2	<3	6	3.60	0.002	0.018	<0.02	<0.01	<2	0.068	0.008	0.14	9.68	<0.02	<0.01	<0.001	<0.01	<0.01	0.05
358719	Drill Core	8.05	<2	7	11	2.19	<0.001	0.018	<0.02	<0.01	<2	0.139	0.011	0.12	7.79	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358720	Drill Core	1.23	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	7	<0.001	<0.001	0.06	0.96	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
358721	Drill Core	8.11	34	<3	13	3.88	0.001	0.023	<0.02	<0.01	<2	0.120	0.013	0.12	8.89	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358722	Drill Core	8.49	<2	<3	5	2.16	<0.001	0.011	<0.02	<0.01	<2	0.057	0.008	0.13	6.56	<0.02	<0.01	<0.001	<0.01	<0.01	0.04
358723	Drill Core	8.21	<2	<3	2	1.25	<0.001	0.013	<0.02	<0.01	<2	0.078	0.007	0.13	6.89	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358724	Drill Core	8.15	<2	<3	7	3.86	0.002	0.021	<0.02	0.02	<2	0.091	0.010	0.15	10.66	<0.02	<0.01	<0.001	<0.01	<0.01	0.05
358725	Rock Pulp	0.04	I.S.	I.S.	I.S.	4.03	<0.001	0.045	<0.02	0.01	<2	0.383	0.026	0.12	11.78	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
358726	Rock Pulp	0.05	I.S.	I.S.	I.S.	0.49	<0.001	0.054	<0.02	0.02	<2	0.223	0.010	0.11	8.30	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
358727	Drill Core	7.34	<2	4	14	0.73	<0.001	0.006	<0.02	0.01	<2	0.101	0.006	0.16	6.69	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358728	Drill Core	7.86	4	9	27	2.48	0.001	0.019	<0.02	0.01	<2	0.103	0.010	0.15	8.15	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358729	Drill Core	7.43	<2	10	5	2.38	0.002	0.021	<0.02	0.01	<2	0.122	0.011	0.16	8.89	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
358730A	Drill Core	7.73	<2	33	<2	1.81	0.001	0.018	<0.02	0.01	<2	0.113	0.008	0.15	7.80	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
358730B	Client Dup		<2	6	13	1.71	0.001	0.020	<0.02	0.01	<2	0.116	0.009	0.16	8.11	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358731	Drill Core	8.32	<2	14	10	1.39	0.001	0.017	<0.02	0.01	<2	0.085	0.008	0.15	7.16	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358732	Drill Core	8.92	<2	10	16	0.59	<0.001	0.016	<0.02	0.01	<2	0.140	0.007	0.16	7.12	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358733	Drill Core	9.20	<2	<3	18	1.07	0.001	0.013	<0.02	0.02	<2	0.100	0.007	0.15	7.64	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358734	Drill Core	7.62	<2	41	27	1.26	<0.001	0.011	<0.02	0.01	<2	0.125	0.009	0.11	6.39	<0.02	<0.01	<0.001	<0.01	<0.01	0.02



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: November 06, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000880.1

Method		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
Unit		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
MDL		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
358706	Drill Core	9.37	<0.01	0.182	15.34	0.04	0.27	0.06	<0.01	<0.01	0.79	0.021	0.075	0.009	0.63	0.98	N.A.
358707	Drill Core	3.36	<0.01	0.219	21.02	0.02	0.16	0.03	<0.01	<0.01	0.78	0.017	0.138	0.009	1.43	2.72	N.A.
358708	Drill Core	2.68	<0.01	0.119	22.71	0.02	0.11	0.02	<0.01	<0.01	0.97	0.026	0.116	0.013	2.18	4.57	N.A.
358709	Drill Core	1.09	0.01	0.173	23.74	0.01	0.10	0.01	<0.01	<0.01	0.62	0.018	0.125	0.011	1.18	3.46	N.A.
358710	Drill Core	0.47	<0.01	0.161	23.75	<0.01	0.06	<0.01	<0.01	<0.01	0.42	0.027	0.119	0.007	1.21	3.38	N.A.
358711	Drill Core	0.67	<0.01	0.203	23.97	0.01	0.08	<0.01	<0.01	<0.01	0.40	0.021	0.140	0.007	1.29	3.58	N.A.
358712	Drill Core	2.15	<0.01	0.098	18.69	0.02	0.10	0.01	<0.01	<0.01	0.77	0.017	0.121	0.011	1.00	2.21	2.89
358713	Drill Core	5.00	<0.01	0.148	16.84	0.03	0.19	0.02	<0.01	<0.01	0.77	0.011	0.099	0.009	0.67	0.95	N.A.
358714	Drill Core	4.28	0.02	0.137	15.40	0.04	0.20	0.04	0.02	<0.01	1.38	0.013	0.080	0.010	2.32	1.71	N.A.
358715	Drill Core	3.98	0.01	0.140	16.17	0.05	0.28	0.04	0.02	<0.01	0.76	0.008	0.091	0.007	1.33	1.42	N.A.
358716	Drill Core	1.59	<0.01	0.129	18.17	0.04	0.21	0.02	0.02	<0.01	0.67	0.004	0.117	0.007	0.91	1.09	N.A.
358717	Drill Core	2.39	<0.01	0.098	16.33	0.04	0.24	0.03	0.02	<0.01	1.56	0.011	0.113	0.010	1.80	0.63	N.A.
358718	Drill Core	8.29	0.01	0.139	12.02	0.06	0.25	0.05	0.02	<0.01	2.59	0.022	0.064	0.009	3.20	0.73	N.A.
358719	Drill Core	5.11	<0.01	0.175	18.15	0.04	0.16	0.02	<0.01	<0.01	1.51	0.014	0.091	0.008	1.23	0.94	N.A.
358720	Drill Core	1.74	0.01	0.002	0.20	0.07	6.08	3.53	1.08	<0.01	<0.01	0.004	0.023	0.002	0.27	0.15	N.A.
358721	Drill Core	7.63	<0.01	0.144	13.09	0.04	0.19	0.03	<0.01	<0.01	2.35	0.029	0.123	0.015	3.43	1.43	N.A.
358722	Drill Core	11.24	<0.01	0.148	12.56	0.05	0.24	0.05	<0.01	<0.01	1.49	0.013	0.052	0.007	1.16	0.47	N.A.
358723	Drill Core	8.10	<0.01	0.137	13.59	0.04	0.22	0.02	<0.01	<0.01	0.85	0.016	0.074	0.007	1.40	1.66	N.A.
358724	Drill Core	5.20	<0.01	0.119	14.06	0.06	0.46	0.09	0.13	<0.01	3.47	0.020	0.067	0.008	0.43	0.40	N.A.
358725	Rock Pulp	1.14	<0.01	0.156	19.44	0.02	0.27	0.05	0.19	<0.01	3.34	0.047	0.382	0.023	1.06	1.50	N.A.
358726	Rock Pulp	4.25	<0.01	0.946	12.67	0.16	3.70	0.27	0.12	<0.01	0.49	0.054	0.182	0.006	0.29	0.24	N.A.
358727	Drill Core	2.42	<0.01	0.121	15.45	0.04	0.27	0.05	0.05	<0.01	0.63	0.006	0.084	0.005	0.26	0.40	N.A.
358728	Drill Core	3.33	<0.01	0.117	13.04	0.04	0.24	0.06	0.04	<0.01	1.86	0.021	0.102	0.009	0.43	0.44	N.A.
358729	Drill Core	2.46	<0.01	0.122	16.60	0.02	0.16	0.04	0.03	<0.01	2.16	0.019	0.124	0.011	0.59	1.15	N.A.
358730A	Drill Core	2.90	<0.01	0.119	13.64	0.04	0.22	0.05	0.04	<0.01	1.50	0.019	0.112	0.008	0.36	0.34	N.A.
358730B	Client Dup	2.98	<0.01	0.123	14.61	0.04	0.24	0.06	0.10	<0.01	1.52	0.019	0.104	0.007	0.33	0.31	N.A.
358731	Drill Core	4.57	<0.01	0.136	13.46	0.04	0.25	0.06	0.05	<0.01	1.17	0.018	0.079	0.007	0.31	0.33	N.A.
358732	Drill Core	4.22	<0.01	0.121	15.03	0.04	0.58	0.05	0.21	<0.01	0.68	0.016	0.121	0.006	0.32	0.43	3.22
358733	Drill Core	2.66	<0.01	0.134	14.78	0.05	0.38	0.05	0.06	<0.01	1.04	0.014	0.082	0.005	0.36	0.40	N.A.
358734	Drill Core	2.22	<0.01	0.118	16.34	0.03	0.24	0.03	0.03	<0.01	1.14	0.011	0.123	0.008	0.34	0.47	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: November 06, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000880.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
358735	Drill Core	8.23	<2	11	12	0.40	<0.001	0.008	<0.02	0.01	<2	0.109	0.007	0.15	6.89	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358736	Drill Core	8.34	4	17	19	2.43	<0.001	0.034	<0.02	0.01	<2	0.216	0.017	0.14	9.93	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358737	Drill Core	8.06	<2	<3	7	1.43	<0.001	0.010	<0.02	0.01	<2	0.107	0.008	0.14	6.90	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358738	Drill Core	9.07	5	6	4	1.55	<0.001	0.010	<0.02	0.01	<2	0.121	0.009	0.14	7.86	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
358739	Drill Core	8.70	<2	4	6	1.25	<0.001	0.012	<0.02	0.02	<2	0.150	0.010	0.15	7.49	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358740	Drill Core	8.60	4	8	8	1.94	0.001	0.012	<0.02	0.02	<2	0.152	0.011	0.15	8.47	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358741	Drill Core	8.24	3	<3	6	1.78	<0.001	0.015	<0.02	0.01	<2	0.139	0.010	0.17	9.01	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358742	Drill Core	8.42	6	12	12	0.41	<0.001	0.013	<0.02	0.01	<2	0.214	0.010	0.14	7.05	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
358743	Drill Core	8.47	8	<3	2	0.41	<0.001	0.008	<0.02	0.02	<2	0.145	0.007	0.17	7.40	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358744	Drill Core	8.63	7	24	14	3.53	0.002	0.029	<0.02	0.01	<2	0.212	0.017	0.16	11.26	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
358745	Drill Core	8.44	4	5	8	0.90	<0.001	0.016	<0.02	0.01	<2	0.113	0.009	0.17	7.59	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
358746	Drill Core	7.99	9	18	22	0.72	<0.001	0.022	<0.02	0.01	<2	0.211	0.009	0.18	7.73	<0.02	<0.01	<0.001	<0.01	<0.01	0.03



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: November 06, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000880.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
358735	Drill Core	2.49	<0.01	0.109	15.96	0.05	0.30	0.05	0.04	<0.01	0.44	0.008	0.086	0.005	0.22	0.30	N.A.
358736	Drill Core	2.28	<0.01	0.117	15.84	0.05	0.31	0.04	0.06	<0.01	1.92	0.035	0.195	0.014	0.48	0.31	N.A.
358737	Drill Core	3.84	<0.01	0.125	13.50	0.06	0.34	0.04	0.07	<0.01	1.12	0.011	0.102	0.007	0.30	0.25	N.A.
358738	Drill Core	2.58	<0.01	0.111	15.11	0.05	0.32	0.03	0.05	<0.01	1.24	0.010	0.100	0.007	0.31	0.33	N.A.
358739	Drill Core	2.65	<0.01	0.127	15.90	0.05	0.28	0.03	0.03	<0.01	1.02	0.013	0.136	0.007	0.31	0.29	N.A.
358740	Drill Core	2.29	<0.01	0.121	15.06	0.05	0.28	0.02	0.04	<0.01	1.50	0.014	0.141	0.009	0.34	0.26	N.A.
358741	Drill Core	2.51	<0.01	0.123	16.03	0.05	0.29	0.03	0.02	<0.01	1.40	0.015	0.115	0.007	0.31	0.28	N.A.
358742	Drill Core	1.66	<0.01	0.110	20.52	0.02	0.15	0.01	<0.01	<0.01	0.43	0.012	0.099	0.004	0.36	0.86	2.85
358743	Drill Core	1.50	<0.01	0.107	16.68	0.05	0.24	0.02	0.02	<0.01	0.42	0.008	0.106	0.004	0.24	0.28	N.A.
358744	Drill Core	1.42	<0.01	0.105	14.47	0.04	0.25	0.02	0.04	<0.01	2.34	0.031	0.192	0.015	0.47	0.28	N.A.
358745	Drill Core	1.30	<0.01	0.120	15.33	0.04	0.24	0.02	0.02	<0.01	0.77	0.016	0.089	0.006	0.24	0.25	N.A.
358746	Drill Core	2.20	<0.01	0.120	16.83	0.04	0.24	0.03	0.03	<0.01	0.72	0.021	0.161	0.006	0.31	0.25	N.A.

QUALITY CONTROL REPORT

SMI08000880.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
Pulp Duplicates																					
358707	Drill Core	6.74	<2	5	10	1.05	<0.001	0.015	<0.02	<0.01	<2	0.173	0.012	0.15	9.77	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 358707	QC	1.09																			
358713	Drill Core	7.41	<2	<3	3	1.08	<0.001	0.010	<0.02	<0.01	<2	0.103	0.009	0.14	7.94	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
REP 358713	QC																				
358726	Rock Pulp	0.05	I.S.	I.S.	I.S.	0.49	<0.001	0.054	<0.02	0.02	<2	0.223	0.010	0.11	8.30	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
REP 358726	QC	I.S. I.S. I.S.																			
358731	Drill Core	8.32	<2	14	10	1.39	0.001	0.017	<0.02	0.01	<2	0.085	0.008	0.15	7.16	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
REP 358731	QC																				
358738	Drill Core	9.07	5	6	4	1.55	<0.001	0.010	<0.02	0.01	<2	0.121	0.009	0.14	7.86	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
REP 358738	QC																				
358743	Drill Core	8.47	8	<3	2	0.41	<0.001	0.008	<0.02	0.02	<2	0.145	0.007	0.17	7.40	<0.02	<0.01	<0.001	<0.01	<0.01	0.03
REP 358743	QC	<0.001 0.008 <0.02 0.02 <2 0.149 0.007 0.17 7.48 <0.02 <0.01 <0.001 <0.01 <0.01 0.03																			
Core Reject Duplicates																					
358720	Drill Core	1.23	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	7	<0.001	<0.001	0.06	0.96	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
DUP 358720	QC	<2 <3 <2 <0.02 <0.001 <0.001 <0.02 <0.01 <2 <0.001 <0.001 0.07 0.94 <0.02 0.08 <0.001 <0.01 <0.01 <0.01																			
Reference Materials																					
STD CDN-PGMS-14	Standard	233 109 431																			
STD CDN-PGMS-14	Standard	237 125 442																			
STD CDN-PGMS-8	Standard	668 373 1342																			
STD CDN-PGMS-8	Standard	867 426 1575																			
STD CSC	Standard	4.31																			
STD CSC	Standard	4.31																			
STD FA10R	Standard	478 451 489																			
STD FA10R	Standard	483 464 496																			
STD FA10R	Standard	438 419 436																			
STD FA10R	Standard	508 469 503																			
STD OREAS76A	Standard	18.18																			
STD OREAS76A	Standard	17.86																			

QUALITY CONTROL REPORT

SMI08000880.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG	
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%		
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
Pulp Duplicates																	
358707	Drill Core	3.36	<0.01	0.219	21.02	0.02	0.16	0.03	<0.01	<0.01	0.78	0.017	0.138	0.009	1.43	2.72	N.A.
REP 358707	QC																
358713	Drill Core	5.00	<0.01	0.148	16.84	0.03	0.19	0.02	<0.01	<0.01	0.77	0.011	0.099	0.009	0.67	0.95	N.A.
REP 358713	QC										0.011	0.098	0.009	0.66	0.94		
358726	Rock Pulp	4.25	<0.01	0.946	12.67	0.16	3.70	0.27	0.12	<0.01	0.49	0.054	0.182	0.006	0.29	0.24	N.A.
REP 358726	QC																
358731	Drill Core	4.57	<0.01	0.136	13.46	0.04	0.25	0.06	0.05	<0.01	1.17	0.018	0.079	0.007	0.31	0.33	N.A.
REP 358731	QC										0.018	0.080	0.007	0.32	0.33		
358738	Drill Core	2.58	<0.01	0.111	15.11	0.05	0.32	0.03	0.05	<0.01	1.24	0.010	0.100	0.007	0.31	0.33	N.A.
REP 358738	QC										0.011	0.103	0.007	0.39	0.47		
358743	Drill Core	1.50	<0.01	0.107	16.68	0.05	0.24	0.02	0.02	<0.01	0.42	0.008	0.106	0.004	0.24	0.28	N.A.
REP 358743	QC	1.53	<0.01	0.111	17.06	0.04	0.24	0.02	0.02	<0.01	0.43						
Core Reject Duplicates																	
358720	Drill Core	1.74	0.01	0.002	0.20	0.07	6.08	3.53	1.08	<0.01	<0.01	0.004	0.023	0.002	0.27	0.15	N.A.
DUP 358720	QC	1.84	<0.01	0.001	0.20	0.07	6.76	3.93	1.12	<0.01	<0.01	0.004	0.026	0.002	0.38	0.20	N.A.
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-14	Standard																
STD CDN-PGMS-8	Standard																
STD CDN-PGMS-8	Standard																
STD CSC	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																
STD OREAS76A	Standard																

QUALITY CONTROL REPORT

SMI08000880.1

		WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD		
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
STD R4T	Standard						0.062	0.515	1.55	3.57	87	0.353	0.040	0.09	24.95	<0.02	0.02	0.018	0.01	<0.01	0.02	
STD R4T	Standard						0.056	0.480	1.50	3.30	85	0.342	0.039	0.09	23.20	<0.02	0.02	0.018	0.01	<0.01	0.01	
STD SF-3A_NI	Standard																					
STD SF-3A_NI	Standard																					
STD SF-3T	Standard						0.031	0.760	0.87	1.09	53	0.351	0.016	0.38	8.16	<0.02	0.04	0.004	<0.01	<0.01	0.01	
STD SF-3T	Standard						0.027	0.712	0.85	0.96	48	0.327	0.016	0.41	7.40	<0.02	0.04	0.004	<0.01	<0.01	0.01	
STD SF-3T Expected							0.032	0.7723	0.961	1.0672	52	0.35	0.0181	0.432	8.33	0.004	0.044	0.00475	0.00111	0.00048	0.0143	
STD R4T Expected							0.062	0.502	1.518	3.376	86	0.348	0.039	0.086	24.07	0.0087	0.0185	0.018	0.0138	0.0018	0.016	
STD CDN-PGMS-14			259	119	451																	
STD CSC Expected						4.25																
STD OREAS76A Expected						18																
STD FA10R Expected			485	472	476																	
STD CDN-PGMS-8 Expected			820	440	1500																	
STD SF-3A_NI Expected																						
BLK	Blank						<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	
BLK	Blank						<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
BLK	Blank					0.03																
BLK	Blank					<0.02																
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
BLK	Blank		<2	<3	<2																	
Prep Wash																						

QUALITY CONTROL REPORT

SMI08000880.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
STD R4T	Standard	2.18	0.04	0.018	1.44	0.21	4.00	0.92	1.14	<0.01	12.18						
STD R4T	Standard	2.10	0.04	0.017	1.35	0.18	3.49	0.84	1.10	<0.01	11.81						
STD SF-3A_NI	Standard											0.768	0.311	0.015	1.56	2.15	
STD SF-3A_NI	Standard											0.009	0.341	0.018	3.89	3.48	
STD SF-3T	Standard	4.01	0.05	0.018	4.51	0.19	5.32	2.04	2.44	<0.01	3.72						
STD SF-3T	Standard	3.94	0.04	0.015	4.36	0.17	4.79	1.78	2.37	<0.01	4.16						
STD SF-3T Expected		4.1	0.06	0.02074	4.67	0.19	5.43	2.06	2.47	0.00043	3.5						
STD R4T Expected		2.166	0.045	0.018	1.384		3.897	0.9	1.153	0.00016							
STD CDN-PGMS-14																	
STD CSC Expected																	
STD OREAS76A Expected																	
STD FA10R Expected																	
STD CDN-PGMS-8 Expected																	
STD SF-3A_NI Expected																0.3205	
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
Prep Wash																	

QUALITY CONTROL REPORT

SMI08000880.1

		WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
G1	Prep Blank	<0.01	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.003	<0.001	0.07	2.30	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank	<0.01	<2	<3	<2	0.07	<0.001	<0.001	<0.02	<0.01	<2	0.003	<0.001	0.07	2.43	<0.02	0.07	<0.001	<0.01	<0.01	<0.01

QUALITY CONTROL REPORT

SMI08000880.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
G1	Prep Blank	2.29	0.07	0.002	0.73	0.22	6.72	2.37	2.68	<0.01	<0.01	<0.001	0.003	<0.001	0.09	0.08	N.A.
G1	Prep Blank	2.46	0.07	0.002	0.81	0.24	7.30	2.55	2.88	<0.01	<0.01	<0.001	0.002	<0.001	0.08	0.07	N.A.

Hole 08-264



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Email Distribution List
 Receiving Lab: Canada-Smithers
 Received: September 08, 2008
 Report Date: October 20, 2008
 Page: 1 of 2

CERTIFICATE OF ANALYSIS

SMI08000884.1

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-264A
 P.O. Number
 Number of Samples: 24

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC:

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	22	Crush split and pulverize drill core to 200 mesh		
3B	22	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	24	Analysis by Leco	0.1	Completed
7TD	24	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	24	Leached with H2O2 + NH4 citrate	1	Completed
Specific Gravity	2	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. ** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 20, 2008

Page: 2 of 2 Part 1

CERTIFICATE OF ANALYSIS

SMI08000884.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
647159	Drill Core	3.20	<2	5	6	0.71	0.001	0.013	<0.02	<0.01	<2	0.154	0.011	0.13	7.50	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
647160	Drill Core	2.62	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	2	<0.001	<0.001	0.07	0.93	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
647161	Drill Core	9.49	2	10	9	1.05	0.002	0.012	<0.02	<0.01	<2	0.147	0.012	0.13	7.83	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
647162	Drill Core	9.82	8	8	8	1.36	0.001	0.021	<0.02	<0.01	<2	0.229	0.016	0.14	10.17	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
647163	Drill Core	10.01	6	7	5	0.58	<0.001	0.007	<0.02	<0.01	<2	0.208	0.011	0.14	8.65	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
647164	Drill Core	10.17	6	11	17	1.29	0.001	0.012	<0.02	<0.01	<2	0.243	0.016	0.15	10.49	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647165	Drill Core	10.14	11	8	7	1.05	<0.001	0.016	<0.02	<0.01	<2	0.205	0.015	0.14	8.92	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647166	Drill Core	9.67	6	28	35	0.59	<0.001	0.011	<0.02	<0.01	<2	0.303	0.013	0.14	8.66	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
647167	Drill Core	9.86	5	26	28	0.85	<0.001	0.014	<0.02	<0.01	<2	0.265	0.016	0.15	9.50	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647168	Drill Core	9.73	3	4	5	0.40	<0.001	0.007	<0.02	<0.01	<2	0.257	0.013	0.15	8.29	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647169	Drill Core	8.66	6	15	16	0.73	<0.001	0.014	<0.02	<0.01	<2	0.254	0.014	0.11	8.64	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647170	Drill Core	9.36	5	22	17	1.14	0.001	0.020	<0.02	<0.01	<2	0.181	0.013	0.12	8.50	<0.02	0.03	<0.001	<0.01	<0.01	0.01
647171	Drill Core	8.72	6	17	23	1.15	<0.001	0.030	<0.02	<0.01	<2	0.285	0.016	0.14	9.09	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647172	Drill Core	9.38	4	29	28	1.07	<0.001	0.024	<0.02	<0.01	<2	0.321	0.016	0.14	8.86	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647173	Drill Core	9.90	4	16	17	0.91	<0.001	0.014	<0.02	<0.01	<2	0.283	0.016	0.14	9.79	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647174	Drill Core	9.42	4	12	11	1.37	<0.001	0.024	<0.02	<0.01	<2	0.237	0.019	0.13	9.58	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647175	Rock Pulp	0.01	I.S.	I.S.	I.S.	0.47	<0.001	0.055	<0.02	0.02	<2	0.246	0.012	0.11	8.59	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
647176	Rock Pulp	0.02	I.S.	I.S.	I.S.	4.29	0.001	0.048	<0.02	<0.01	<2	0.427	0.029	0.13	13.30	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647177	Drill Core	9.29	6	17	16	1.82	<0.001	0.060	<0.02	<0.01	<2	0.285	0.024	0.13	9.36	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647178	Drill Core	8.80	9	33	35	1.86	<0.001	0.055	<0.02	<0.01	<2	0.331	0.024	0.10	8.24	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647179	Drill Core	8.88	6	32	35	1.37	<0.001	0.059	<0.02	<0.01	<2	0.348	0.016	0.10	6.65	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647180	Drill Core	8.60	12	71	83	1.73	<0.001	0.126	<0.02	<0.01	3	0.663	0.024	0.11	7.96	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647181	Drill Core	8.57	14	48	60	1.50	<0.001	0.096	<0.02	<0.01	<2	0.500	0.023	0.10	7.81	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647182	Drill Core	9.26	6	38	46	1.90	<0.001	0.065	<0.02	<0.01	<2	0.429	0.024	0.09	8.30	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: October 20, 2008

Page: 2 of 2 Part 2

CERTIFICATE OF ANALYSIS

SMI08000884.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
647159	Drill Core	4.82	<0.01	0.160	19.90	0.03	0.22	0.05	<0.01	<0.01	0.67	0.009	0.124	0.008	0.35	0.63	N.A.
647160	Drill Core	1.81	0.01	<0.001	0.16	0.06	6.38	3.61	1.13	<0.01	<0.01	<0.001	<0.001	<0.001	0.02	<0.01	N.A.
647161	Drill Core	5.59	<0.01	0.195	19.06	0.04	0.28	0.06	<0.01	<0.01	0.85	0.011	0.124	0.009	0.34	0.58	N.A.
647162	Drill Core	3.05	<0.01	0.173	21.80	0.03	0.14	0.02	<0.01	<0.01	1.18	0.018	0.185	0.011	0.58	1.03	N.A.
647163	Drill Core	2.08	<0.01	0.174	22.94	0.02	0.10	0.02	<0.01	<0.01	0.56	0.006	0.148	0.006	0.45	1.07	N.A.
647164	Drill Core	1.87	<0.01	0.153	23.94	0.01	0.07	0.02	<0.01	<0.01	1.11	0.010	0.178	0.009	0.63	1.32	N.A.
647165	Drill Core	1.85	<0.01	0.143	24.02	0.01	0.08	0.02	<0.01	<0.01	0.93	0.013	0.144	0.009	0.54	1.42	N.A.
647166	Drill Core	4.25	0.01	0.101	19.78	0.09	1.03	0.01	0.02	<0.01	0.54	0.009	0.240	0.008	0.48	0.89	N.A.
647167	Drill Core	1.95	<0.01	0.181	24.06	0.01	0.09	0.02	<0.01	<0.01	0.79	0.014	0.206	0.009	0.54	1.02	N.A.
647168	Drill Core	2.24	<0.01	0.129	24.49	0.01	0.09	0.02	<0.01	<0.01	0.41	0.007	0.180	0.007	0.45	1.01	N.A.
647169	Drill Core	0.55	<0.01	0.104	23.14	0.01	0.15	<0.01	<0.01	<0.01	0.69	0.010	0.221	0.011	0.40	0.85	N.A.
647170	Drill Core	4.82	0.04	0.087	15.66	0.13	2.81	0.29	0.18	<0.01	0.95	0.019	0.175	0.012	0.37	0.66	N.A.
647171	Drill Core	0.36	<0.01	0.182	22.57	0.01	0.15	<0.01	<0.01	<0.01	1.04	0.021	0.265	0.013	0.47	1.10	N.A.
647172	Drill Core	0.89	<0.01	0.206	24.29	0.01	0.09	<0.01	<0.01	<0.01	0.92	0.021	0.275	0.012	0.60	1.24	3.05
647173	Drill Core	0.15	<0.01	0.193	24.19	<0.01	0.06	<0.01	<0.01	<0.01	0.84	0.012	0.253	0.012	0.54	1.24	N.A.
647174	Drill Core	0.06	<0.01	0.127	23.89	0.01	0.13	<0.01	<0.01	<0.01	1.29	0.022	0.210	0.015	0.55	1.34	N.A.
647175	Rock Pulp	4.36	<0.01	1.071	13.67	0.18	4.05	0.32	0.11	<0.01	0.51	0.058	0.188	0.007	0.38	0.43	N.A.
647176	Rock Pulp	1.18	<0.01	0.177	21.11	0.02	0.28	0.03	0.09	<0.01	3.64	0.051	0.410	0.024	1.16	1.56	N.A.
647177	Drill Core	0.02	<0.01	0.196	25.25	<0.01	0.05	<0.01	<0.01	<0.01	1.65	0.066	0.266	0.021	0.69	1.57	N.A.
647178	Drill Core	0.03	<0.01	0.144	23.12	<0.01	0.14	<0.01	<0.01	<0.01	1.60	0.050	0.327	0.023	0.86	1.44	N.A.
647179	Drill Core	3.94	0.01	0.097	20.36	0.05	1.63	<0.01	<0.01	<0.01	1.25	0.061	0.356	0.016	0.79	1.67	N.A.
647180	Drill Core	0.05	<0.01	0.213	24.43	<0.01	0.04	<0.01	<0.01	<0.01	1.52	0.131	0.614	0.021	1.29	3.30	N.A.
647181	Drill Core	0.07	<0.01	0.128	23.37	<0.01	0.03	<0.01	<0.01	<0.01	1.39	0.094	0.443	0.020	1.56	3.88	N.A.
647182	Drill Core	0.27	<0.01	0.204	23.80	<0.01	0.12	<0.01	0.03	<0.01	1.58	0.068	0.393	0.019	0.91	1.94	3.02

QUALITY CONTROL REPORT

SMI08000884.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
Pulp Duplicates																					
647166	Drill Core	9.67	6	28	35	0.59	<0.001	0.011	<0.02	<0.01	<2	0.303	0.013	0.14	8.66	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
REP 647166	QC																				
647177	Drill Core	9.29	6	17	16	1.82	<0.001	0.060	<0.02	<0.01	<2	0.285	0.024	0.13	9.36	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
REP 647177	QC					1.81															
Reference Materials																					
STD CDN-PGMS-14	Standard		269	109	453																
STD CSC	Standard					4.45															
STD FA10R	Standard		451	452	458																
STD OREAS76A	Standard					17.74															
STD R4T	Standard					0.063	0.512	1.56	3.52	91	0.350	0.039	0.09	24.68	<0.02	0.02	0.018	0.02	<0.01	0.02	
STD SF-3A_NI	Standard																				
STD SF-3T	Standard					0.032	0.770	0.95	1.09	53	0.346	0.018	0.42	8.02	<0.02	0.04	0.004	<0.01	<0.01	0.01	
STD SF-3T Expected						0.032	0.7723	0.961	1.0672	52	0.35	0.0181	0.432	8.33	0.004	0.044	0.00475	0.00111	0.00048	0.0143	
STD R4T Expected						0.062	0.502	1.518	3.376	86	0.348	0.039	0.086	24.07	0.0087	0.0185	0.018	0.0138	0.0018	0.016	
STD FA10R Expected			485	472	476																
STD CDN-PGMS-14			259	119	451																
STD SF-3A_NI Expected																					
STD CSC Expected						4.25															
STD OREAS76A Expected						18															
BLK	Blank					<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank																				
BLK	Blank					<0.02															
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.002	<0.001	0.08	2.46	<0.02	0.06	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank	<0.01	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.002	<0.001	0.07	2.35	<0.02	0.07	<0.001	<0.01	<0.01	<0.01

QUALITY CONTROL REPORT

SMI08000884.1

Method		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
Unit		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
Pulp Duplicates																	
647166	Drill Core	4.25	0.01	0.101	19.78	0.09	1.03	0.01	0.02	<0.01	0.54	0.009	0.240	0.008	0.48	0.89	N.A.
REP 647166	QC											0.009	0.248	0.009	0.50	0.94	
647177	Drill Core	0.02	<0.01	0.196	25.25	<0.01	0.05	<0.01	<0.01	<0.01	1.65	0.066	0.266	0.021	0.69	1.57	N.A.
REP 647177	QC																
Reference Materials																	
STD CDN-PGMS-14	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD OREAS76A	Standard																
STD R4T	Standard	2.13	0.04	0.018	1.42	0.20	3.93	0.90	1.15	<0.01	13.44						
STD SF-3A_NI	Standard											0.787	0.313	0.015	1.52	2.02	
STD SF-3T	Standard	4.01	0.05	0.020	4.56	0.20	5.49	2.08	2.44	<0.01	4.29						
STD SF-3T Expected		4.1	0.06	0.02074	4.67	0.19	5.43	2.06	2.47	0.00043	3.5						
STD R4T Expected		2.166	0.045	0.018	1.384		3.897	0.9	1.153	0.00016							
STD FA10R Expected																	
STD CDN-PGMS-14																	
STD SF-3A_NI Expected												0.3205					
STD CSC Expected																	
STD OREAS76A Expected																	
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank																
Prep Wash																	
G1	Prep Blank	2.32	0.07	0.001	0.81	0.25	6.62	2.51	2.91	<0.01	<0.01	<0.001	<0.001	<0.001	0.06	0.04	N.A.
G1	Prep Blank	2.35	0.07	0.002	0.85	0.23	6.48	2.59	2.94	<0.01	<0.01	<0.001	<0.001	<0.001	0.06	0.05	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Submitted By: Email Distribution List
 Receiving Lab: Canada-Smithers
 Received: September 06, 2008
 Report Date: November 13, 2008
 Page: 1 of 3

CERTIFICATE OF ANALYSIS

SMI08000876.1

CLIENT JOB INFORMATION

Project: Turnagain
 Shipment ID: C08-264B
 P.O. Number
 Number of Samples: 48

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
 STOR-RJT Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Hard Creek Nickel Corporation
 1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7
 Canada

CC: Email Distribution List

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status
R150	44	Crush split and pulverize drill core to 200 mesh		
3B	48	Fire assay fusion Au Pt Pd by ICP-ES	30	Completed
2A (Total S)	48	Analysis by Leco	0.1	Completed
7TD	48	4 Acid digestion ICP-ES analysis	0.5	Completed
8NiS	48	Leached with H2O2 + NH4 citrate	1	Completed
Specific Gravity	2	Specific Gravity on Drill Core		Completed

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. ** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

ACME ANALYTICAL LABORATORIES LTD.

www.acmelab.com

Client:

Hard Creek Nickel Corporation

1060 - 1090 W. Georgia St.
Vancouver BC V6E 3V7 Canada

Project:

Turnagain

Report Date:

November 13, 2008

Page:

2 of 3

Part 1

CERTIFICATE OF ANALYSIS

SMI08000876.1

Method	WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
647183	Drill Core	10.26	19	79	99	1.00	<0.001	0.084	<0.02	<0.01	<2	0.421	0.017	0.11	7.73	<0.02	0.01	<0.001	<0.01	<0.01	<0.01
647184	Drill Core	10.26	<2	54	72	1.54	<0.001	0.105	<0.02	<0.01	2	0.597	0.022	0.11	8.44	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647185	Drill Core	10.22	<2	40	61	1.84	<0.001	0.095	<0.02	<0.01	<2	0.474	0.024	0.11	8.96	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647186	Drill Core	9.81	<2	28	35	0.84	<0.001	0.087	<0.02	<0.01	<2	0.426	0.017	0.11	7.83	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647187	Drill Core	10.57	3	58	78	1.59	<0.001	0.064	<0.02	<0.01	<2	0.346	0.021	0.11	9.36	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647188	Drill Core	10.65	4	9	20	1.39	<0.001	0.031	<0.02	<0.01	<2	0.224	0.016	0.11	9.23	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647189	Drill Core	10.42	<2	21	26	0.87	<0.001	0.023	<0.02	<0.01	<2	0.291	0.015	0.12	8.63	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647190	Drill Core	2.56	<2	<3	5	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.002	<0.001	0.06	1.03	<0.02	0.08	<0.001	<0.01	<0.01	<0.01
647191	Drill Core	10.37	<2	17	31	1.52	<0.001	0.032	<0.02	<0.01	<2	0.329	0.019	0.12	9.32	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647192	Drill Core	10.89	<2	10	15	1.86	<0.001	0.032	<0.02	<0.01	<2	0.178	0.022	0.12	10.15	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647193	Drill Core	10.15	5	11	16	2.16	<0.001	0.047	<0.02	<0.01	<2	0.248	0.022	0.11	10.12	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647194	Drill Core	10.40	<2	14	22	0.46	<0.001	0.012	<0.02	<0.01	<2	0.250	0.013	0.11	6.97	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647195	Drill Core	9.67	<2	42	49	1.02	<0.001	0.059	<0.02	<0.01	<2	0.349	0.018	0.10	7.46	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647196	Drill Core	9.35	<2	17	38	0.75	<0.001	0.055	<0.02	<0.01	<2	0.259	0.016	0.10	7.38	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647197	Drill Core	9.45	3	32	53	1.27	<0.001	0.038	<0.02	<0.01	<2	0.401	0.019	0.11	8.33	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647198	Drill Core	9.95	<2	23	23	1.67	<0.001	0.038	<0.02	<0.01	<2	0.288	0.022	0.10	8.75	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647199	Drill Core	8.90	<2	19	46	0.69	<0.001	0.036	<0.02	<0.01	<2	0.335	0.016	0.10	6.66	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647200	Rock Pulp	0.05	I.S.	I.S.	I.S.	1.30	<0.001	0.028	<0.02	<0.01	<2	0.238	0.015	0.11	8.08	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647201	Rock Pulp	0.05	I.S.	I.S.	I.S.	0.42	<0.001	0.054	<0.02	0.02	<2	0.230	0.011	0.11	8.84	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
647202	Drill Core	9.97	<2	85	106	0.32	<0.001	0.049	<0.02	<0.01	<2	0.278	0.013	0.11	6.46	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647203	Drill Core	9.40	<2	35	49	0.26	<0.001	0.017	<0.02	<0.01	<2	0.295	0.014	0.12	6.73	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647204	Drill Core	9.67	<2	39	63	0.26	<0.001	0.024	<0.02	<0.01	<2	0.304	0.014	0.12	6.80	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647205	Drill Core	9.59	<2	38	46	0.33	<0.001	0.022	<0.02	<0.01	<2	0.300	0.014	0.13	7.10	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647206	Drill Core	9.25	<2	39	46	0.46	<0.001	0.012	<0.02	<0.01	<2	0.289	0.011	0.11	6.85	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647207	Drill Core	8.89	<2	28	48	0.59	<0.001	0.024	<0.02	<0.01	<2	0.393	0.012	0.12	6.91	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647208	Drill Core	7.70	15	82	95	1.43	<0.001	0.034	<0.02	<0.01	<2	0.608	0.018	0.07	7.32	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647209	Drill Core	9.58	3	22	32	0.98	<0.001	0.035	<0.02	<0.01	<2	0.272	0.014	0.14	7.74	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647210A	Drill Core	7.98	<2	28	33	0.86	<0.001	0.021	<0.02	<0.01	<2	0.207	0.011	0.13	7.31	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647210B	Client Dup		<2	25	30	0.78	<0.001	0.021	<0.02	<0.01	<2	0.202	0.011	0.13	7.23	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647211	Drill Core	9.44	<2	7	22	1.66	0.001	0.029	<0.02	<0.01	<2	0.238	0.017	0.08	9.67	<0.02	<0.01	<0.001	<0.01	<0.01	0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: November 13, 2008

Page: 2 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000876.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
647183	Drill Core	0.98	0.01	0.249	23.22	0.03	0.75	0.03	0.06	<0.01	0.80	0.087	0.342	0.012	0.85	1.71	N.A.
647184	Drill Core	0.44	<0.01	0.149	24.39	<0.01	0.04	<0.01	<0.01	<0.01	1.17	0.098	0.463	0.014	0.96	1.28	N.A.
647185	Drill Core	0.13	<0.01	0.154	24.24	<0.01	0.03	<0.01	<0.01	<0.01	1.33	0.093	0.413	0.018	1.20	2.29	N.A.
647186	Drill Core	0.52	<0.01	0.229	25.21	<0.01	0.05	<0.01	<0.01	<0.01	0.67	0.086	0.301	0.009	0.87	1.53	N.A.
647187	Drill Core	0.25	<0.01	0.199	24.46	<0.01	0.05	<0.01	<0.01	<0.01	1.23	0.065	0.293	0.015	0.82	1.78	N.A.
647188	Drill Core	0.36	<0.01	0.287	24.49	<0.01	0.05	<0.01	<0.01	<0.01	1.01	0.029	0.194	0.011	0.62	1.66	N.A.
647189	Drill Core	0.31	<0.01	0.222	24.68	<0.01	0.05	<0.01	<0.01	<0.01	0.72	0.022	0.210	0.008	0.63	1.39	N.A.
647190	Drill Core	1.95	0.02	0.002	0.28	0.07	7.75	3.56	1.12	<0.01	<0.01	<0.001	0.002	<0.001	0.04	0.03	N.A.
647191	Drill Core	0.11	<0.01	0.192	24.91	<0.01	0.03	<0.01	<0.01	<0.01	1.05	0.031	0.269	0.012	0.71	1.40	N.A.
647192	Drill Core	0.22	<0.01	0.329	24.23	<0.01	0.06	<0.01	<0.01	<0.01	1.30	0.031	0.156	0.015	0.70	1.53	3.22
647193	Drill Core	0.15	<0.01	0.383	23.02	<0.01	0.06	<0.01	<0.01	<0.01	1.48	0.046	0.221	0.017	1.00	2.32	N.A.
647194	Drill Core	0.17	<0.01	0.224	23.82	<0.01	0.05	<0.01	<0.01	<0.01	0.38	0.011	0.161	0.006	0.56	1.93	N.A.
647195	Drill Core	0.19	<0.01	0.217	24.13	<0.01	0.06	<0.01	<0.01	<0.01	0.84	0.058	0.284	0.011	0.98	2.38	N.A.
647196	Drill Core	0.17	<0.01	0.304	23.75	<0.01	0.07	<0.01	<0.01	<0.01	0.62	0.058	0.200	0.010	0.82	2.27	N.A.
647197	Drill Core	0.14	<0.01	0.229	24.84	<0.01	0.05	<0.01	<0.01	<0.01	0.85	0.035	0.310	0.012	0.85	2.00	N.A.
647198	Drill Core	0.05	<0.01	0.226	23.19	<0.01	0.05	<0.01	<0.01	<0.01	1.17	0.039	0.253	0.015	0.86	1.96	N.A.
647199	Drill Core	0.04	<0.01	0.179	23.91	<0.01	0.05	<0.01	<0.01	<0.01	0.58	0.035	0.283	0.010	0.86	2.92	N.A.
647200	Rock Pulp	0.68	<0.01	0.208	21.44	0.02	0.29	<0.01	0.07	<0.01	0.99	0.028	0.218	0.011	0.79	2.10	N.A.
647201	Rock Pulp	4.21	<0.01	1.294	12.99	0.18	4.15	0.33	0.11	<0.01	0.38	0.053	0.179	0.007	0.31	0.24	N.A.
647202	Drill Core	0.04	<0.01	0.233	24.17	<0.01	0.06	<0.01	<0.01	<0.01	0.27	0.045	0.165	0.007	0.53	2.01	N.A.
647203	Drill Core	0.51	<0.01	0.298	24.17	0.01	0.08	<0.01	<0.01	<0.01	0.23	0.017	0.180	0.007	0.60	2.13	N.A.
647204	Drill Core	0.03	<0.01	0.121	24.34	<0.01	0.04	<0.01	<0.01	<0.01	0.23	0.022	0.204	0.008	0.53	2.30	N.A.
647205	Drill Core	0.08	<0.01	0.189	24.72	<0.01	0.07	<0.01	<0.01	<0.01	0.28	0.020	0.237	0.009	0.51	1.96	N.A.
647206	Drill Core	0.10	<0.01	0.093	23.63	0.01	0.07	<0.01	<0.01	<0.01	0.39	0.010	0.257	0.010	0.55	1.90	N.A.
647207	Drill Core	0.29	<0.01	0.167	23.24	0.01	0.09	<0.01	<0.01	<0.01	0.54	0.020	0.375	0.011	0.72	2.62	N.A.
647208	Drill Core	0.06	<0.01	0.171	20.73	0.01	0.10	<0.01	<0.01	<0.01	1.13	0.027	0.545	0.016	1.04	2.15	N.A.
647209	Drill Core	0.44	<0.01	0.201	22.33	0.01	0.09	<0.01	<0.01	<0.01	0.83	0.033	0.330	0.015	0.87	2.47	N.A.
647210A	Drill Core	0.83	<0.01	0.170	20.73	0.02	0.12	<0.01	<0.01	<0.01	0.69	0.018	0.200	0.010	0.78	2.10	N.A.
647210B	Client Dup	0.84	<0.01	0.165	20.63	0.02	0.12	<0.01	<0.01	<0.01	0.68	0.018	0.196	0.010	0.77	1.87	N.A.
647211	Drill Core	1.59	<0.01	0.189	18.69	0.03	0.21	0.01	<0.01	<0.01	1.22	0.022	0.236	0.016	0.66	1.53	N.A.



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: November 13, 2008

Page: 3 of 3 Part 1

CERTIFICATE OF ANALYSIS

SMI08000876.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
647212	Drill Core	9.43	<2	57	55	2.11	<0.001	0.053	<0.02	<0.01	<2	0.281	0.013	0.10	8.18	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
647213	Drill Core	9.38	10	95	86	2.16	<0.001	0.087	<0.02	<0.01	<2	0.195	0.020	0.10	11.51	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647214	Drill Core	7.64	14	82	57	1.54	<0.001	0.074	<0.02	0.01	<2	0.199	0.014	0.11	9.64	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647215	Drill Core	8.44	15	162	90	3.10	0.001	0.114	<0.02	<0.01	<2	0.241	0.023	0.11	12.74	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
647216	Drill Core	9.41	5	7	15	1.40	<0.001	0.020	<0.02	0.01	<2	0.190	0.016	0.14	8.16	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647217	Drill Core	10.50	4	4	14	3.22	0.004	0.054	<0.02	0.01	<2	0.079	0.011	0.14	10.35	<0.02	0.02	<0.001	<0.01	<0.01	0.04
647218	Drill Core	8.27	<2	4	6	0.67	<0.001	0.017	<0.02	<0.01	<2	0.232	0.012	0.11	6.18	<0.02	<0.01	<0.001	<0.01	<0.01	0.01
647219	Drill Core	9.11	<2	6	7	0.17	<0.001	0.002	<0.02	<0.01	<2	0.280	0.011	0.09	5.19	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647220	Drill Core	2.32	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	1.08	<0.02	0.08	<0.001	<0.01	<0.01	<0.01
647221	Drill Core	10.39	<2	5	2	0.08	<0.001	<0.001	<0.02	<0.01	<2	0.270	0.012	0.12	6.47	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647222	Drill Core	9.30	<2	6	2	0.07	<0.001	<0.001	<0.02	<0.01	<2	0.269	0.011	0.11	5.89	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647223	Drill Core	10.59	<2	3	3	0.03	<0.001	<0.001	<0.02	<0.01	<2	0.270	0.011	0.11	6.32	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647224	Drill Core	9.66	<2	4	2	0.05	<0.001	<0.001	<0.02	<0.01	<2	0.268	0.011	0.11	5.96	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647225	Rock Pulp	0.05	I.S.	I.S.	I.S.	4.18	0.002	0.047	<0.02	<0.01	<2	0.433	0.027	0.12	12.95	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647226	Rock Pulp	0.03	I.S.	I.S.	I.S.	0.48	<0.001	0.051	<0.02	0.02	<2	0.233	0.011	0.11	8.77	<0.02	<0.01	<0.001	<0.01	<0.01	0.02
647227	Drill Core	10.61	<2	7	7	0.02	<0.001	<0.001	<0.02	<0.01	<2	0.293	0.011	0.11	6.08	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647228	Drill Core	10.20	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	0.286	0.011	0.11	5.93	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
647229	Drill Core	2.53	<2	<3	<2	0.07	<0.001	<0.001	<0.02	<0.01	<2	0.289	0.010	0.10	5.28	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01



ACME ANALYTICAL LABORATORIES LTD.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Hard Creek Nickel Corporation**

1060 - 1090 W. Georgia St.
 Vancouver BC V6E 3V7 Canada

Project: Turnagain

Report Date: November 13, 2008

Page: 3 of 3 Part 2

CERTIFICATE OF ANALYSIS

SMI08000876.1

Method		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
Analyte		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
Unit		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
MDL		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
647212	Drill Core	3.54	<0.01	0.130	17.97	0.05	0.37	0.01	<0.01	<0.01	1.60	0.046	0.267	0.012	0.51	0.77	2.80
647213	Drill Core	2.44	<0.01	0.179	18.06	0.03	0.23	0.02	<0.01	<0.01	1.50	0.064	0.179	0.018	0.42	0.66	N.A.
647214	Drill Core	1.06	<0.01	0.223	18.87	0.02	0.43	<0.01	<0.01	<0.01	1.17	0.056	0.194	0.013	0.50	0.98	N.A.
647215	Drill Core	2.69	<0.01	0.236	19.70	0.04	0.26	0.02	<0.01	<0.01	2.43	0.111	0.238	0.022	1.47	1.82	N.A.
647216	Drill Core	0.49	<0.01	0.298	24.76	0.03	0.26	<0.01	0.01	<0.01	1.26	0.017	0.156	0.012	0.98	2.67	N.A.
647217	Drill Core	10.19	0.03	0.101	7.78	0.15	2.21	0.40	0.63	<0.01	2.52	0.057	0.071	0.009	2.08	0.18	N.A.
647218	Drill Core	1.35	<0.01	0.519	23.81	0.09	0.80	0.02	0.26	<0.01	0.65	0.017	0.172	0.008	1.32	6.27	N.A.
647219	Drill Core	0.66	<0.01	0.172	26.74	0.03	0.26	<0.01	0.05	<0.01	0.19	0.001	0.167	0.006	0.66	4.52	N.A.
647220	Drill Core	2.03	0.02	<0.001	0.23	0.08	8.31	3.72	1.24	<0.01	<0.01	<0.001	<0.001	<0.001	0.09	0.04	N.A.
647221	Drill Core	1.23	<0.01	0.182	26.58	0.03	0.25	0.01	0.03	<0.01	0.08	<0.001	0.094	0.004	0.70	2.99	N.A.
647222	Drill Core	1.19	<0.01	0.235	26.07	0.03	0.32	0.03	0.04	<0.01	0.08	<0.001	0.109	0.004	0.72	3.24	N.A.
647223	Drill Core	1.30	<0.01	0.306	26.91	0.03	0.31	0.01	<0.01	<0.01	0.06	<0.001	0.075	0.003	0.86	3.45	N.A.
647224	Drill Core	1.55	<0.01	0.173	26.81	0.04	0.33	0.02	0.01	<0.01	0.05	<0.001	0.081	0.003	0.80	3.52	N.A.
647225	Rock Pulp	1.16	<0.01	0.240	21.97	0.02	0.28	0.03	0.10	<0.01	3.17	0.050	0.391	0.025	2.13	3.03	N.A.
647226	Rock Pulp	4.20	<0.01	1.320	13.46	0.19	4.25	0.33	0.11	<0.01	0.45	0.057	0.186	0.007	0.52	0.53	N.A.
647227	Drill Core	1.39	<0.01	0.150	27.41	0.03	0.26	0.01	<0.01	<0.01	0.03	<0.001	0.068	0.003	0.74	3.12	N.A.
647228	Drill Core	1.00	<0.01	0.104	27.94	0.03	0.22	0.01	0.03	<0.01	0.04	<0.001	0.077	0.003	0.76	3.35	N.A.
647229	Drill Core	0.95	<0.01	0.066	26.64	0.02	0.18	<0.01	0.05	<0.01	0.07	<0.001	0.109	0.004	0.61	3.76	N.A.

QUALITY CONTROL REPORT

SMI08000876.1

Method	WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD		
Analyte	Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V			
Unit	kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%			
MDL	0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01			
Pulp Duplicates																							
REP G1	QC																						
647196	Drill Core	9.35	<2	17	38	0.75	<0.001	0.055	<0.02	<0.01	<2	0.259	0.016	0.10	7.38	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01		
REP 647196	QC					0.81																	
647206	Drill Core	9.25	<2	39	46	0.46	<0.001	0.012	<0.02	<0.01	<2	0.289	0.011	0.11	6.85	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01		
REP 647206	QC					<2	40	41															
647211	Drill Core	9.44	<2	7	22	1.66	0.001	0.029	<0.02	<0.01	<2	0.238	0.017	0.08	9.67	<0.02	<0.01	<0.001	<0.01	<0.01	0.01		
REP 647211	QC					0.001	0.029	<0.02	<0.01	<2	0.242	0.018	0.08	9.90	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	0.01		
647212	Drill Core	9.43	<2	57	55	2.11	<0.001	0.053	<0.02	<0.01	<2	0.281	0.013	0.10	8.18	<0.02	<0.01	<0.001	<0.01	<0.01	0.01		
REP 647212	QC																						
647215	Drill Core	8.44	15	162	90	3.10	0.001	0.114	<0.02	<0.01	<2	0.241	0.023	0.11	12.74	<0.02	<0.01	<0.001	<0.01	<0.01	0.02		
REP 647215	QC																						
647219	Drill Core	9.11	<2	6	7	0.17	<0.001	0.002	<0.02	<0.01	<2	0.280	0.011	0.09	5.19	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01		
REP 647219	QC					0.16																	
647222	Drill Core	9.30	<2	6	2	0.07	<0.001	<0.001	<0.02	<0.01	<2	0.269	0.011	0.11	5.89	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01		
REP 647222	QC					<0.001	0.001	<0.02	<0.01	<2	0.271	0.011	0.11	5.90	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01		
Core Reject Duplicates																							
647184	Drill Core	10.26	<2	54	72	1.54	<0.001	0.105	<0.02	<0.01	2	0.597	0.022	0.11	8.44	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01		
DUP 647184	QC					<2	47	74	1.56	<0.001	0.103	<0.02	<0.01	<2	0.603	0.023	0.11	8.49	<0.02	<0.01	<0.001	<0.01	<0.01
647218	Drill Core	8.27	<2	4	6	0.67	<0.001	0.017	<0.02	<0.01	<2	0.232	0.012	0.11	6.18	<0.02	<0.01	<0.001	<0.01	<0.01	0.01		
DUP 647218	QC					<2	<3	6	0.71	<0.001	0.017	<0.02	<0.01	<2	0.228	0.012	0.11	6.19	<0.02	<0.01	<0.001	<0.01	<0.01
Reference Materials																							
STD CDN-PGMS-8	Standard					875	448	1514															
STD CDN-PGMS-8	Standard					883	418	1400															
STD CSC	Standard								4.01														
STD CSC	Standard								4.16														
STD FA10R	Standard					449	422	459															
STD FA10R	Standard					426	421	449															
STD FA10R	Standard																						

QUALITY CONTROL REPORT

SMI08000876.1

Method	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG	
Analyte	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG	
Unit	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%		
MDL	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0	
Pulp Duplicates																	
REP G1	QC										<0.001	<0.001	<0.001	0.02	0.01		
647196	Drill Core	0.17	<0.01	0.304	23.75	<0.01	0.07	<0.01	<0.01	<0.01	0.62	0.058	0.200	0.010	0.82	2.27	N.A.
REP 647196	QC																
647206	Drill Core	0.10	<0.01	0.093	23.63	0.01	0.07	<0.01	<0.01	<0.01	0.39	0.010	0.257	0.010	0.55	1.90	N.A.
REP 647206	QC																
647211	Drill Core	1.59	<0.01	0.189	18.69	0.03	0.21	0.01	<0.01	<0.01	1.22	0.022	0.236	0.016	0.66	1.53	N.A.
REP 647211	QC	1.64	<0.01	0.192	19.27	0.03	0.22	0.01	<0.01	<0.01	1.23						
647212	Drill Core	3.54	<0.01	0.130	17.97	0.05	0.37	0.01	<0.01	<0.01	1.60	0.046	0.267	0.012	0.51	0.77	2.80
REP 647212	QC										0.046	0.263	0.011	0.51	0.77		
647215	Drill Core	2.69	<0.01	0.236	19.70	0.04	0.26	0.02	<0.01	<0.01	2.43	0.111	0.238	0.022	1.47	1.82	N.A.
REP 647215	QC										0.108	0.233	0.022	2.07	2.98		
647219	Drill Core	0.66	<0.01	0.172	26.74	0.03	0.26	<0.01	0.05	<0.01	0.19	0.001	0.167	0.006	0.66	4.52	N.A.
REP 647219	QC																
647222	Drill Core	1.19	<0.01	0.235	26.07	0.03	0.32	0.03	0.04	<0.01	0.08	<0.001	0.109	0.004	0.72	3.24	N.A.
REP 647222	QC	1.19	<0.01	0.247	26.69	0.03	0.32	0.03	0.03	<0.01	0.08						
Core Reject Duplicates																	
647184	Drill Core	0.44	<0.01	0.149	24.39	<0.01	0.04	<0.01	<0.01	<0.01	1.17	0.098	0.463	0.014	0.96	1.28	N.A.
DUP 647184	QC	0.42	<0.01	0.150	24.83	<0.01	0.03	<0.01	<0.01	<0.01	1.18	0.108	0.515	0.016	1.10	1.56	N.A.
647218	Drill Core	1.35	<0.01	0.519	23.81	0.09	0.80	0.02	0.26	<0.01	0.65	0.017	0.172	0.008	1.32	6.27	N.A.
DUP 647218	QC	1.39	<0.01	0.523	24.34	0.09	0.80	0.02	0.26	<0.01	0.65	0.016	0.168	0.008	1.23	6.01	N.A.
Reference Materials																	
STD CDN-PGMS-8	Standard																
STD CDN-PGMS-8	Standard																
STD CSC	Standard																
STD CSC	Standard																
STD FA10R	Standard																
STD FA10R	Standard																
STD FA10R	Standard																

QUALITY CONTROL REPORT

SMI08000876.1

		WGHT	3B	3B	3B 2A Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	
		Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V
		kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%
		0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01
STD OREAS76A	Standard					17.87															
STD OREAS76A	Standard					17.67															
STD R4T	Standard						0.061	0.498	1.45	3.36	83	0.337	0.038	0.09	23.38	<0.02	0.02	0.017	0.01	<0.01	0.01
STD R4T	Standard						0.063	0.518	1.58	3.40	88	0.355	0.040	0.09	24.17	<0.02	0.02	0.018	0.02	<0.01	0.02
STD SF-3A_NI	Standard																				
STD SF-3A_NI	Standard																				
STD SF-3T	Standard						0.031	0.750	0.90	1.06	51	0.325	0.016	0.42	7.90	<0.02	0.04	0.004	<0.01	<0.01	0.01
STD SF-3T	Standard						0.033	0.784	0.97	1.08	53	0.353	0.018	0.44	8.22	<0.02	0.04	0.004	<0.01	<0.01	0.01
STD CSC Expected						4.25															
STD OREAS76A Expected						18															
STD SF-3T Expected							0.032	0.7723	0.961	1.0672	52	0.35	0.0181	0.432	8.33	0.004	0.044	0.00475	0.00111	0.00048	0.0143
STD R4T Expected							0.062	0.502	1.518	3.376	86	0.348	0.039	0.086	24.07	0.0087	0.0185	0.018	0.0138	0.0018	0.016
STD SF-3A_NI Expected																					
STD FA10R Expected			485	472	476																
STD CDN-PGMS-8 Expected			820	440	1500																
BLK	Blank						<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
BLK	Blank					<0.02															
BLK	Blank					<0.02															
BLK	Blank						<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	<0.01	<0.01	<0.02	<0.01	<0.001	<0.01	<0.01	<0.01
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank																				
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
BLK	Blank		<2	<3	<2																
Prep Wash																					
G1	Prep Blank	<0.01	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.46	<0.02	0.07	<0.001	<0.01	<0.01	<0.01
G1	Prep Blank	<0.01	<2	<3	<2	<0.02	<0.001	<0.001	<0.02	<0.01	<2	<0.001	<0.001	0.07	2.32	<0.02	0.07	<0.001	<0.01	<0.01	<0.01

QUALITY CONTROL REPORT

SMI08000876.1

		7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
		Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
		0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
STD OREAS76A	Standard																
STD OREAS76A	Standard																
STD R4T	Standard	2.11	0.04	0.017	1.35	0.19	3.84	0.89	1.10	<0.01	11.61						
STD R4T	Standard	2.20	0.05	0.017	1.40	0.20	3.98	0.92	1.18	<0.01	12.91						
STD SF-3A_NI	Standard											0.691	0.312	0.014	1.65	2.33	
STD SF-3A_NI	Standard											0.013	0.330	0.016	3.49	3.33	
STD SF-3T	Standard	3.96	0.05	0.016	4.31	0.18	5.30	2.06	2.38	<0.01	3.61						
STD SF-3T	Standard	4.10	0.06	0.019	4.62	0.20	5.45	2.08	2.46	<0.01	4.06						
STD CSC Expected																	
STD OREAS76A Expected																	
STD SF-3T Expected		4.1	0.06	0.02074	4.67	0.19	5.43	2.06	2.47	0.00043	3.5						
STD R4T Expected		2.166	0.045	0.018	1.384		3.897	0.9	1.153	0.00016							
STD SF-3A_NI Expected												0.3205					
STD FA10R Expected																	
STD CDN-PGMS-8 Expected																	
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																
BLK	Blank																
BLK	Blank	<0.01	<0.01	<0.001	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01						
BLK	Blank																
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank											<0.001	<0.001	<0.001	<0.01	<0.01	
BLK	Blank																
BLK	Blank																
Prep Wash																	
G1	Prep Blank	2.62	0.11	<0.001	0.71	0.24	8.12	2.62	2.85	<0.01	<0.01						N.A.
G1	Prep Blank	2.56	0.08	0.001	0.70	0.23	8.08	2.60	2.74	<0.01	<0.01	<0.001	<0.001	<0.001	0.04	0.02	N.A.

QUALITY CONTROL REPORT

SMI08000876.1

WGHT	3B	3B	3B 2A	Leco	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD
Wgt	Au	Pt	Pd	TOT/S	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Sr	Cd	Sb	Bi	V	
kg	ppb	ppb	ppb	%	%	%	%	%	gm/mt	%	%	%	%	%	%	%	%	%	%	
0.01	2	3	2	0.02	0.001	0.001	0.02	0.01	2	0.001	0.001	0.01	0.01	0.02	0.01	0.001	0.01	0.01	0.01	
G1	Prep Blank																			

QUALITY CONTROL REPORT

SMI08000876.1

	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	7TD	8NiS	8NiS	8NiS	8NiS	8NiS	G8SG
	Ca	P	Cr	Mg	Ti	Al	Na	K	W	S	Cu	Ni	Co	Fe	Mg	SG
	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	
	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.001	0.001	0.001	0.01	0.01	0
G1	Prep Blank										<0.001	<0.001	<0.001	0.03	0.02	

Appendix F

Exploration Work type	Comment	Days		Totals
Personnel (Name)* / Position	Field Days (list actual days)	Days	Rate	Subtotal*
Tony Hitchins - Chief Geologist	Jun 13-27, Jul 9-25, Aug 15-31, Sep 1-3	52	\$650.00	\$33,800.00
Greg Ross - Camp Manager/Geologist	Jun 4-30, Jul 1-18, 28-31, Aug 1-27	76	\$500.00	\$38,000.00
Erik Scheel - Project Geologist	Jun 4-30, Jul 1-11, 21-31, Aug 1-27	76	\$500.00	\$38,000.00
Catherine Juelfs - Geologist	Jun 9-11, 25-30, Jul 1-31, Aug 1-18	58	\$380.00	\$22,040.00
Don Cambridge - First Aid/Cook	Jun 18-30, Jul 1-11, Aug 13-31, Sep1-3	46	\$500.00	\$23,000.00
Bob Mackie - Pad Builder/Skilled Labour	May 29-31, Jun 1-30, Jul 4-31, Aug 1-6, 13-31, Sep 1-3	89	\$500.00	\$44,500.00
Florence Gaal - First Aid/Cook	May 30-31, Jun 1-19, Jul 11-31, Aug 1-13	28	\$350.00	\$9,800.00
Sean Hawkins - Geotechnician	Jun 4-14, 17-20, 26-30, Jul 1-18, 23-31	47	\$250.00	\$11,750.00
Elizabeth Blackburn - Bull Cook	Jun 4-18, Jul 13-18, 23-31, Aug 1	31	\$250.00	\$7,750.00
Geraldine Etzertza - Bull Cook	Jun 18-30, Jul 1-12, Aug 1-25	50	\$250.00	\$12,500.00
Claude Bisaillon - Geotechnical Engineer	Jun 18-27, Aug 6-18	23	\$500.00	\$11,500.00
Bonnie Sedore - Core Splitter	Aug 15-26	12	\$300.00	\$3,600.00
Doug Johnson - Core Splitter	Jun 9-30, Jul 1-4	26	\$300.00	\$7,800.00
				\$264,040.00
Office Studies	List Personnel			
Literature search			\$0.00	\$0.00
Database compilation	Sandy Smeeton	10	\$350.00	\$3,500.00
Computer modelling			\$0.00	\$0.00
Reprocessing of data			\$0.00	\$0.00
General research			\$0.00	\$0.00
Report preparation			\$0.00	\$0.00
				\$3,500.00
				\$3,500.00
Geochemical Surveying	Number of Samples	No.	Rate	Subtotal
Drill (cuttings, core, etc.)		1056	\$87.47	\$92,368.32
Stream sediment			\$0.00	\$0.00
Soil	<i>note: This is for assays or laboratory costs</i>		\$0.00	\$0.00
Rock			\$0.00	\$0.00
Water			\$0.00	\$0.00
Biogeochemistry			\$0.00	\$0.00
Whole rock			\$0.00	\$0.00
				\$92,368.32
				\$92,368.32
Drilling	No. of Holes, Size of Core and Metres	No. m	Rate /m	Subtotal
Diamond NQ	14 holes	3933.10	\$128.00	\$503,436.80
Diamond HQ	2 holes	172.22	\$228.00	\$39,266.16
Reverse circulation (RC)			\$0.00	\$0.00
Rotary air blast (RAB)			\$0.00	\$0.00
				\$542,702.96
				\$542,702.96
Transportation		No.	Rate	Subtotal
Airfare			\$0.00	\$0.00
Taxi			\$0.00	\$0.00
Truck rental			\$0.00	\$0.00
Kilometres			\$0.00	\$0.00
ATV			\$0.00	\$0.00
Fuel	Diesel: 11,269L@\$1.29/L + 22,520L@\$1.37/L + 10,609L@1.41/L		\$0.00	\$60,348.09
Helicopter (hours)	Bell 206 \$875/hr + fuel	175.5	\$875.00	\$153,562.50
Fuel (litres/hour)	Bell 206 114L/hr	20007.0	\$1.70	\$34,011.90
				\$247,922.49
				\$247,922.49
Accommodation & Food	Rates per day			
Hotel			\$0.00	\$0.00
Meals	3438 meals	3438.00	\$12.00	\$41,256.00
				\$41,256.00
				\$41,256.00
Miscellaneous				
Telephone+Internet Service	2.5 months of service	2.5	\$85.00	\$212.50
Core boxes and Sample bags and tags				\$14,316.06
				\$14,528.56
				\$14,528.56
Equipment Rentals				
Field Gear (Specify)	Reflex Maxibor 101 days	101	\$228.80	\$23,108.80
				\$23,108.80
				\$23,108.80
Freight, rock samples	sample shipment to Smithers, Camp material from Dease Lake			\$85,300.47
Machinery for road work, drill moves	D6 cat, backhoe for trail building and reclamation		\$0.00	\$113,625.46
BC Certified Surveyors	Surveying of Drill Collars		\$0.00	\$9,728.25
				\$208,654.18
				\$208,654.18
TOTAL Expenditures				\$1,438,081.31


Appendix G

STATEMENT OF QUALIFICATIONS

GREG ROSS

I, GREG ROSS, of 201 – 3707 Cambie Street, Vancouver, BC, hereby certify that:

1. I am a Hard Creek Nickel Corp. staff geologist.
2. I hold a B.Sc. in Earth Science from the University of Victoria, awarded in 2006.
3. I hold the designation of Geoscientist-in-Training (GIT) from the Association of Professional Engineers and Geoscientists of the Province of British Columbia, awarded in 2008.
4. This report is based on my examination of data collected in 2007 while working for Hard Creek Nickel Corp., having observed and performed a portion of the work reported herein.


Gregory Ross

29 July 2009
Date

STATEMENT OF QUALIFICATIONS

J. ERIK SCHEEL

I, J. ERIK SCHEEL., of Apt. 207, 43 E 15th Avenue, Vancouver, BC, hereby certify that:

1. I am a full time geologist, presently retained by Hard Creek Nickel Corporation.
2. I hold a B.Sc.H in Geological Sciences from the University of Alberta, awarded in 2004, and a M.Sc. in Geological Sciences from the University of British Columbia, awarded in 2007
3. I have read and understood the report, have written the hole descriptions, conclusions, and recommendations, and made editorial changes based on my knowledge of the deposit and having observed and performed a portion of the work herein during my time as a geologist with Hard Creek Nickel Corp. and during my M.Sc. thesis research.



J. Erik Scheel

Wed July 29, 2009

Date