

The diamond drill core from the 2008 Meridian Project work is stored on a private residence located at 448,360mE / 5620710mN (NAD 83/zone 11) in the village of Beaton, BC.

BC Geological Survey
Assessment Report
30955b

CERTIFICATE OF ASSAY AK 2008-0669

Manson Creek Resources

Suite 500, 926 - 5 Avenue S.W.

Calgary, AB

T2P 0N7

16-Jun-08

No. of samples received: 68

Sample Type: Core

Project: Meridian

Submitted by: Dustin Rainey

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	G20454	<0.03	<0.001
2	G20455	<0.03	<0.001
3	G20456	<0.03	<0.001
4	G20457	<0.03	<0.001
5	G20458	<0.03	<0.001
6	G20459	<0.03	<0.001
7	G20460	<0.03	<0.001
8	G20461	<0.03	<0.001
9	G20462	<0.03	<0.001
10	G20463	<0.03	<0.001
11	G20464	<0.03	<0.001
12	G20465	<0.03	<0.001
13	G20466	<0.03	<0.001
14	G20467	0.03	0.001
15	G20468	0.42	0.012
16	G20469	0.13	0.004
17	G20470	<0.03	<0.001
18	G20471	<0.03	<0.001
19	G20472	0.86	0.025
20	G20473	0.26	0.008
21	G20474	0.36	0.010
22	G20475	0.99	0.029
23	G20476	0.16	0.005
24	G20477	0.05	0.001
25	G20478	0.14	0.004
26	G20479	1.81	0.053
27	G20480	0.76	0.022
28	G20481	0.08	0.002
29	G20482	0.14	0.004
30	G20483	0.12	0.003
31	G20484	0.24	0.007

ECO TECH LABORATORY LTD.

Jutta Jealouse

B.C. Certified Assayer

Manson Creek Resources AK8-0669

16-Jun-08

ET #.	Tag #	Au (g/t)	Au (oz/t)
32	G20485	0.44	0.013
33	G20486	0.34	0.010
34	G20487	0.33	0.010
35	G20488	<0.03	<0.001
36	G20489	0.32	0.009
37	G20490	0.43	0.013
38	G20491	<0.03	<0.001
39	G20492	<0.03	<0.001
40	G20493	0.26	0.008
41	G20494	0.19	0.006
42	G20495	<0.03	<0.001
43	G20496	0.28	0.008
44	G20497	0.04	0.001
45	G20498	0.10	0.003
46	G20499	<0.03	<0.001
47	G20500	<0.03	<0.001
48	81701	0.11	0.003
49	81702	0.52	0.015
50	81703	0.95	0.028
51	81704	0.22	0.006
52	81705	<0.03	<0.001
53	81706	<0.03	<0.001
54	81707	0.56	0.016
55	81708	<0.03	<0.001
56	81709	0.27	0.008
57	81710	0.55	0.016
58	81711	<0.03	<0.001
59	81712	0.06	0.002
60	81713	<0.03	<0.001
61	81714	0.05	0.001
62	81715	<0.03	<0.001
63	81716	0.06	0.002
64	81717	0.25	0.007
65	81718	0.46	0.013
66	81719	0.04	0.001
67	81720	0.11	0.003
68	81721	0.04	0.001

QC DATA:

Repeat:

1	G20454	<0.03	<0.001
10	G20463	<0.03	<0.001
15	G20468	0.49	0.014
19	G20472	0.92	0.027
22	G20475	1.04	0.030
26	G20479	1.78	0.052
34	G20487	0.29	0.008
36	G20489	0.36	0.010
45	G20498	0.09	0.003
50	81703	1.00	0.029

ECO TECH LABORATORY LTD.

Jutta Jealouse
B.C. Certified Assayer

16-Jun-08

Manson Creek Resources AK8-0669

ET #.	Tag #	Au (g/t)	Au (oz/t)
54	81707	0.58	0.017
57	81710	0.56	0.016
65	81718	0.42	0.012

Resplit:

1	G20454	<0.03	<0.001
36	G20489	0.30	0.009

Standard:

OXI67	1.83	0.053
OXI67	1.79	0.052

ECO TECH LABORATORY LTD.

Jutta Jealouse
B.C. Certified Assayer

JJ/nw
XLS/07

ECO TECH LABORATORY LTD.

10041 Dallas Drive

KAMLOOPS, B.C.

V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 2008- 0669

Manson Creek Resources

Suite 500, 926 - 5 Avenue S.W.

Calgary, AB

T2P 0N7

Phone: 250-573-5700

Fax : 250-573-4557

No. of samples received: 68

Sample Type: Core

Project: Meridian

Submitted by: Dustin Rainey

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	G20454	<0.2	0.72	20	60	<5	0.77	<1	13	77	14	2.87	30	0.66	425	<1	0.02	27	710	22	<5	<20	46	0.02	<10	6	<10	<1	45
2	G20455	<0.2	0.59	15	50	<5	0.57	<1	11	43	11	2.50	20	0.56	353	<1	0.01	19	660	20	<5	<20	34	0.02	<10	5	<10	2	41
3	G20456	<0.2	0.44	20	40	20	0.98	<1	10	94	6	2.51	20	0.54	404	<1	0.02	21	570	22	<5	<20	93	0.02	<10	5	<10	2	39
4	G20457	<0.2	0.48	10	65	<5	0.40	<1	11	60	7	2.81	30	0.41	428	<1	0.01	21	660	18	<5	<20	16	0.02	<10	3	<10	1	37
5	G20458	<0.2	0.21	25	50	5	0.44	<1	10	96	4	2.56	20	0.33	464	<1	0.01	18	530	14	<5	<20	26	0.02	<10	2	<10	2	40
6	G20459	<0.2	0.19	35	35	<5	2.12	<1	5	75	2	1.22	20	0.73	306	<1	0.02	8	300	10	5	<20	186	0.01	<10	3	<10	6	3
7	G20460	<0.2	0.77	10	55	15	1.08	<1	13	67	12	3.23	10	0.84	532	1	0.01	26	580	28	5	<20	95	0.02	<10	5	<10	2	49
8	G20461	<0.2	0.56	25	50	10	0.77	<1	12	70	8	2.90	20	0.60	461	<1	0.01	19	650	20	<5	<20	64	0.02	<10	4	<10	2	38
9	G20462	<0.2	0.41	<5	45	20	0.78	<1	10	60	8	2.70	20	0.57	449	<1	0.01	18	610	14	<5	<20	58	0.02	<10	3	<10	<1	35
10	G20463	<0.2	0.38	<5	50	5	0.87	<1	9	73	7	2.36	20	0.56	437	1	0.02	14	630	16	<5	<20	76	0.02	<10	3	<10	3	35
11	G20464	<0.2	0.52	10	65	<5	0.55	<1	12	62	32	2.74	30	0.65	347	<1	0.01	23	700	20	<5	<20	40	0.02	<10	3	<10	3	43
12	G20465	<0.2	0.15	30	35	<5	1.60	<1	9	102	9	2.80	<10	0.53	597	<1	0.02	17	340	10	<5	<20	130	0.02	<10	1	<10	4	26
13	G20466	<0.2	0.21	35	35	<5	3.95	<1	6	61	2	2.41	<10	1.15	451	<1	0.03	20	1590	10	5	<20	339	0.02	<10	9	<10	9	10
14	G20467	<0.2	0.22	40	45	5	1.32	<1	8	85	3	1.18	<10	0.37	223	<1	0.02	16	390	10	<5	<20	103	0.01	<10	2	<10	3	2
15	G20468	<0.2	0.15	65	20	20	2.12	<1	7	117	4	1.89	<10	0.74	305	<1	0.05	18	340	10	10	<20	211	0.01	<10	4	<10	3	4
16	G20469	<0.2	0.23	65	55	10	2.31	<1	15	87	16	3.50	<10	0.87	445	1	0.02	32	740	16	<5	<20	220	0.02	<10	3	<10	3	19
17	G20470	<0.2	0.18	30	40	<5	1.28	<1	15	96	9	2.21	<10	0.49	336	1	0.01	25	400	12	<5	<20	112	0.01	<10	2	<10	3	6
18	G20471	<0.2	0.19	20	35	<5	1.04	<1	8	98	5	1.63	<10	0.37	294	<1	0.01	14	360	10	<5	<20	79	0.01	<10	2	<10	3	4
19	G20472	0.4	0.23	115	50	10	1.70	<1	21	79	9	4.35	<10	0.51	391	2	0.04	46	590	22	<5	<20	178	0.03	<10	5	<10	3	18
20	G20473	0.2	0.15	65	30	<5	1.38	<1	8	133	4	2.00	<10	0.36	305	<1	0.04	17	130	12	<5	<20	120	0.01	<10	3	<10	2	7
21	G20474	0.2	0.18	110	50	15	1.42	<1	12	138	18	2.96	<10	0.73	488	<1	0.02	31	170	12	<5	<20	180	0.02	<10	3	<10	3	29
22	G20475	0.3	0.20	180	45	<5	2.48	<1	17	104	68	3.44	<10	1.06	553	1	0.02	36	120	16	<5	<20	333	0.02	<10	3	<10	3	19
23	G20476	0.2	0.24	140	60	15	0.94	<1	18	65	34	3.81	<10	0.96	525	1	0.02	38	380	22	5	<20	97	0.02	<10	3	<10	<1	37
24	G20477	<0.2	0.20	90	55	20	1.19	<1	13	83	22	2.83	<10	0.71	541	<1	0.02	28	300	12	<5	<20	129	0.02	<10	2	<10	1	19
25	G20478	<0.2	0.14	65	30	<5	2.50	<1	10	100	29	2.66	<10	1.04	594	<1	0.03	21	80	24	<5	<20	321	0.02	<10	3	<10	2	40

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC DATA:																													
Repeat:																													
1	G20454	<0.2	0.69	20	70	<5	0.77	<1	13	75	14	2.83	20	0.66	422	<1	0.02	24	700	26	<5	<20	49	0.02	<10	6	<10	3	42
10	G20463	<0.2	0.37	5	50	<5	0.87	<1	10	70	6	2.38	20	0.56	441	<1	0.02	15	630	14	<5	<20	70	0.02	<10	3	<10	2	35
19	G20472	0.4	0.23	125	55	5	1.71	<1	21	76	9	4.37	<10	0.52	391	3	0.04	46	600	24	<5	<20	185	0.03	<10	4	<10	3	18
36	G20489	0.2	0.27	100	60	20	1.87	<1	17	93	35	3.72	<10	1.13	592	1	0.02	41	320	18	10	<20	257	0.02	<10	3	<10	3	85
45	G20498	0.2	0.21	60	50	15	1.53	<1	12	83	29	2.93	<10	0.79	510	2	0.02	27	430	16	<5	<20	134	0.02	<10	2	<10	2	48
54	81707	0.3	0.21	40	55	15	1.96	<1	11	147	21	2.66	<10	0.74	484	<1	0.02	20	700	20	<5	<20	251	0.02	<10	3	<10	6	79
Resplit:																													
1	G20454	<0.2	0.65	20	60	<5	0.77	<1	13	74	13	2.74	20	0.65	410	<1	0.01	23	680	22	<5	<20	53	0.02	<10	5	<10	2	42
36	G20489	0.2	0.25	105	55	15	1.80	<1	17	78	37	3.80	<10	1.12	600	1	0.02	43	360	20	5	<20	244	0.02	<10	2	<10	3	79
Standard:																													
Pb129a		12.3	0.85	15	75	<5	0.46	55	6	11	1410	1.60	<10	0.69	350	4	0.03	3	450	6136	15	<20	41	0.05	<10	17	<10	<1	9991
Pb129a		11.9	0.86	15	75	<5	0.48	54	6	11	1392	1.59	<10	0.69	348	4	0.03	3	430	6180	10	<20	36	0.06	<10	17	<10	<1	9908

JJ/nw
df/669s
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

CERTIFICATE OF ASSAY AK 2008-948

Manson Creek Resources

Suite 500, 926 - 5 Avenue S.W.

Calgary, AB

T2P 0N7

22-Aug-08

No. of samples received: 97

Sample Type: Core

Submitted by: Dustin Rainey

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	81722	<0.03	<0.001
2	81723	<0.03	<0.001
3	81724	<0.03	<0.001
4	81725	<0.03	<0.001
5	81726	<0.03	<0.001
6	81727	<0.03	<0.001
7	81728	<0.03	<0.001
8	81729	<0.03	<0.001
9	81730	<0.03	<0.001
10	81731	<0.03	<0.001
11	81732	<0.03	<0.001
12	81733	<0.03	<0.001
13	81734	<0.03	<0.001
14	81735	<0.03	<0.001
15	81736	0.03	0.001
16	81737	0.04	0.001
17	81738	<0.03	<0.001
18	81739	0.31	0.009
19	81740	0.53	0.015
20	81741	<0.03	<0.001
21	81742	<0.03	<0.001
22	81743	<0.03	<0.001
23	81744	<0.03	<0.001
24	81745	<0.03	<0.001
25	81746	<0.03	<0.001
26	81747	<0.03	<0.001
27	81748	<0.03	<0.001
28	81749	<0.03	<0.001
29	81750	<0.03	<0.001
30	81751	<0.03	<0.001
31	81752	<0.03	<0.001
32	81753	0.35	0.010

ECO TECH LABORATORY LTD.

Jutta Jealouse

B.C. Certified Assayer

Manson Creek Resources AK8-0948

22-Aug-08

ET #.	Tag #	Au (g/t)	Au (oz/t)
33	81754	0.27	0.008
34	81755	0.15	0.004
35	81756	<0.03	<0.001
36	81757	<0.03	<0.001
37	81759	<0.03	<0.001
38	81760	0.03	0.001
39	81761	<0.03	<0.001
40	81762	0.04	0.001
41	81763	0.55	0.016
42	81764	1.03	0.030
43	81765	1.83	0.053
44	81766	<0.03	<0.001
45	81767	0.04	0.001
46	81768	0.08	0.002
47	81769	<0.03	<0.001
48	81770	<0.03	<0.001
49	81771	<0.03	<0.001
50	81772	<0.03	<0.001
51	81773	0.34	0.010
52	81774	0.26	0.008
53	81775	3.86	0.113
54	81776	5.94	0.173
55	81777	0.06	0.002
56	81778	0.05	0.001
57	81779	<0.03	<0.001
58	81780	0.17	0.005
59	81781	0.19	0.006
60	81782	0.12	0.003
61	81783	0.04	0.001
62	81784	<0.03	<0.001
63	81785	0.07	0.002
64	81786	0.04	0.001
65	81787	0.18	0.005
66	81788	0.04	0.001
67	81789	0.10	0.003
68	81790	<0.03	<0.001
69	81791	0.13	0.004
70	81792	0.21	0.006
71	81793	0.07	0.002
72	81794	<0.03	<0.001
73	81795	0.04	0.001
74	81796	0.04	0.001
75	81797	0.09	0.003
76	81798	<0.03	<0.001
77	81799	0.04	0.001
78	81800	<0.03	<0.001

ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

ET #.	Tag #	Au (g/t)	Au (oz/t)
79	81801	<0.03	<0.001
80	81802	0.04	0.001
81	81803	0.04	0.001
82	81804	0.06	0.002
83	81805	0.06	0.002
84	81806	0.06	0.002
85	81807	0.35	0.010
86	81808	0.62	0.018
87	81809	0.04	0.001
88	81810	<0.03	<0.001
89	81811	<0.03	<0.001
90	81812	<0.03	<0.001
91	81813	<0.03	<0.001
92	81814	<0.03	<0.001
93	81815	<0.03	<0.001
94	81816	<0.03	<0.001
95	81817	<0.03	<0.001
96	81818	<0.03	<0.001
97	81819	<0.03	<0.001

QC DATA:**Repeat:**

1	81722	<0.03	<0.001
10	81731	<0.03	<0.001
19	81740	0.59	0.017
32	81753	0.35	0.010
36	81757	<0.03	<0.001
42	81764	1.16	0.034
43	81765	1.95	0.057
45	81767	0.06	0.002
53	81775	4.04	0.118
54	81776	6.26	0.183
71	81793	0.11	0.003
80	81802	0.05	0.001
86	81808	0.67	0.020
89	81811	<0.03	<0.001

Resplit:

1	81722	<0.03	<0.001
36	81757	<0.03	<0.001
71	81793	0.09	0.003

Standard:

OXI67	1.81	0.053
OXI67	1.76	0.051
OXI67	1.79	0.052

JJ/ap
XLS/07**ECO TECH LABORATORY LTD.**Jutta Jealous
B.C. Certified Assayer

ECO TECH LABORATORY LTD.

10041 Dallas Drive

KAMLOOPS, B.C.

V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 2008- 948

Manson Creek Resources

Suite 500, 926 - 5 Avenue S.W.

Calgary, AB

T2P 0N7

Phone: 250-573-5700

Fax : 250-573-4557

No. of samples received: 97

Sample Type: Core

Submitted by: Dustin Rainey

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	81722	<0.2	0.35	15	50	<5	0.65	<1	5	96	8	1.44	30	0.35	341	2	0.02	10	440	18	5	<20	50	<0.01	<10	7	<10	3	25
2	81723	<0.2	0.60	15	65	5	0.62	<1	10	85	23	2.56	20	0.60	420	3	0.01	23	410	22	20	<20	61	0.01	<10	7	<10	1	44
3	81724	<0.2	0.53	10	60	<5	1.06	<1	9	59	15	2.36	30	0.65	453	2	0.02	20	490	16	20	<20	84	0.01	<10	8	<10	3	39
4	81725	<0.2	0.82	20	55	<5	0.63	<1	12	66	17	2.94	30	0.68	374	2	0.01	27	520	18	15	<20	53	0.01	<10	10	<10	<1	60
5	81726	<0.2	0.70	20	60	15	0.60	<1	12	63	32	2.54	30	0.62	367	3	0.01	25	450	18	20	<20	40	0.01	<10	9	<10	1	46
6	81727	<0.2	0.28	20	55	<5	0.58	<1	10	62	8	2.95	30	0.75	446	3	0.02	19	460	10	15	<20	34	0.02	<10	6	<10	2	26
7	81728	<0.2	0.26	30	55	10	0.96	<1	8	78	3	2.50	30	0.39	495	3	0.02	18	420	10	15	<20	75	0.01	<10	7	<10	4	17
8	81729	<0.2	0.23	20	30	<5	1.55	<1	5	79	3	1.59	20	0.62	353	6	0.02	9	480	8	15	<20	113	<0.01	<10	6	<10	6	10
9	81730	<0.2	0.20	45	25	10	2.04	<1	6	110	3	1.60	20	0.58	389	1	0.01	15	380	8	20	<20	126	0.01	<10	6	<10	3	8
10	81731	<0.2	0.25	45	45	10	2.42	1	11	87	3	2.28	10	0.82	457	2	0.02	25	360	10	25	<20	164	0.01	<10	7	<10	3	13
11	81732	<0.2	0.28	50	40	10	2.73	<1	11	70	3	1.92	20	0.93	382	3	0.01	27	760	12	25	<20	229	0.01	<10	9	<10	5	16
12	81733	<0.2	0.29	50	45	<5	1.13	<1	12	79	4	1.87	30	0.60	344	1	0.02	26	430	10	5	<20	80	0.01	<10	7	<10	4	12
13	81734	<0.2	0.28	55	50	5	0.87	<1	13	58	7	3.01	30	0.85	450	2	0.01	28	430	10	20	<20	59	0.01	<10	6	<10	3	19
14	81735	<0.2	0.29	75	65	15	1.65	2	17	50	4	3.22	40	1.11	634	3	<0.01	43	480	8	25	<20	111	0.02	<10	6	<10	2	21
15	81736	<0.2	0.14	50	15	10	6.41	2	9	45	2	3.44	<10	2.49	800	3	0.06	33	1070	8	40	<20	617	0.02	<10	13	<10	8	19
16	81737	<0.2	0.17	100	20	10	5.12	2	16	40	1	3.00	<10	1.91	662	5	0.06	53	1330	8	35	<20	484	0.02	<10	13	<10	8	15
17	81738	<0.2	0.12	45	10	10	4.50	<1	5	47	2	2.25	<10	1.74	595	1	0.08	21	660	8	25	<20	430	0.02	<10	9	<10	5	14
18	81739	0.2	0.22	40	55	5	1.25	1	12	108	10	2.80	<10	0.65	324	4	0.02	25	190	14	25	<20	139	0.01	<10	6	<10	3	23
19	81740	0.2	0.23	45	50	10	1.29	<1	11	106	14	2.90	<10	0.70	364	3	0.02	20	430	12	10	<20	132	0.02	<10	6	<10	2	32
20	81741	<0.2	0.26	75	65	10	3.15	3	30	70	64	4.86	<10	1.21	886	6	0.02	75	820	14	35	<20	233	0.02	<10	12	<10	2	62
21	81742	<0.2	0.26	15	55	15	0.90	<1	12	63	26	3.29	20	0.80	361	4	0.01	22	270	14	15	<20	63	0.02	<10	5	<10	<1	48
22	81743	<0.2	0.27	45	55	5	2.18	2	19	67	30	3.64	<10	0.89	787	4	0.02	44	450	16	25	<20	136	0.02	<10	7	<10	1	50
23	81744	0.4	0.25	20	50	5	0.56	<1	11	110	12	2.79	20	0.72	410	2	0.01	21	280	24	10	<20	37	0.02	<10	6	<10	1	32
24	81745	<0.2	0.27	15	50	10	0.41	1	12	59	14	3.07	30	0.80	358	2	0.01	22	310	14	15	<20	22	0.01	<10	5	<10	<1	42
25	81746	0.2	0.31	30	60	20	2.13	1	16	76	23	3.72	<10	0.97	463	4	0.02	32	920	16	25	<20	165	0.02	<10	8	<10	1	33
26	81747	0.2	0.27	50	60	<5	0.61	<1	14	81	3	2.65	30	0.74	370	3	0.01	28	340	10	15	<20	46	0.01	<10	7	<10	2	19
27	81748	<0.2	0.10	10	20	10	0.68	<1	4	146	4	2.31	<10	0.66	316	2	0.01	14	250	8	10	<20	65	0.01	<10	5	<10	<1	15
28	81749	0.2	0.20	30	40	<5	1.19	<1	11	103	7	1.78	<10	0.52	243	2	0.01	25	230	14	10	<20	111	<0.01	<10	6	<10	3	10
29	81750	0.3	0.27	40	50	10	1.23	1	13	105	9	1.93	<10	0.49	231	3	0.02	29	320	14	10	<20	130	<0.01	<10	7	<10	3	14
30	81751	0.3	0.22	20	45	10	0.56	<1	14	79	10	2.57	10	0.54	283	3	<0.01	28	310	18	20	<20	45	<0.01	<10	5	<10	<1	15

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
31	81752	0.2	0.26	20	45	10	0.84	<1	11	132	11	2.22	<10	0.49	332	5	0.01	23	280	10	15	<20	64	0.01	<10	6	<10	2	18
32	81753	<0.2	0.07	65	15	<5	0.99	<1	5	188	5	1.41	<10	0.35	172	2	0.04	18	50	8	15	<20	115	<0.01	<10	4	<10	2	5
33	81754	<0.2	0.12	80	30	5	0.93	<1	5	159	4	1.48	<10	0.29	218	2	0.05	16	60	6	10	<20	83	<0.01	<10	5	<10	1	7
34	81755	<0.2	0.22	60	45	10	1.00	<1	9	105	10	2.27	<10	0.50	330	2	0.02	22	320	10	10	<20	83	0.01	<10	5	<10	2	19
35	81756	0.3	0.24	60	55	10	0.45	2	16	96	36	3.67	20	0.90	435	5	0.02	41	400	36	25	<20	35	0.01	<10	5	<10	2	100
36	81757	0.2	0.30	35	65	15	0.33	2	14	56	27	3.34	30	0.83	397	4	0.01	30	390	34	20	<20	11	0.01	<10	6	<10	<1	73
37	81759	0.2	0.30	30	75	10	0.49	<1	14	86	21	3.38	30	0.82	463	2	0.02	28	380	20	10	<20	20	0.02	<10	6	<10	<1	68
38	81760	0.3	0.23	50	55	15	0.78	2	18	83	48	4.14	20	1.03	526	4	0.01	41	300	36	20	<20	73	0.02	<10	5	<10	1	97
39	81761	0.2	0.33	40	70	15	0.49	3	19	80	28	4.54	30	1.13	460	4	0.01	39	470	26	30	<20	38	0.02	<10	6	<10	<1	97
40	81762	0.2	0.23	65	45	10	0.81	2	14	130	23	3.45	20	0.85	440	4	0.01	35	210	18	20	<20	83	0.01	<10	5	<10	<1	48
41	81763	0.4	0.25	45	50	10	0.65	<1	12	94	28	3.16	20	0.74	473	3	0.02	27	370	16	10	<20	55	0.01	<10	6	<10	1	69
42	81764	0.6	0.20	75	45	<5	0.79	1	17	77	25	3.73	<10	0.88	608	4	0.01	35	210	16	20	<20	82	0.02	<10	6	<10	<1	73
43	81765	0.8	0.21	85	55	15	1.40	3	19	73	34	4.64	<10	1.09	675	6	0.01	46	100	40	35	<20	186	0.02	<10	5	<10	2	119
44	81766	0.6	0.25	50	60	10	1.10	2	23	107	31	4.15	<10	1.06	658	4	0.01	46	260	30	25	<20	105	0.02	<10	6	<10	<1	75
45	81767	0.2	0.40	30	55	10	1.05	<1	14	78	27	3.16	10	0.84	717	4	0.02	29	240	26	25	<20	81	0.02	<10	8	<10	<1	67
46	81768	0.3	0.22	40	45	15	1.74	1	14	96	22	3.31	<10	0.92	802	3	0.02	30	250	32	25	<20	132	0.02	<10	7	<10	1	58
47	81769	0.2	0.92	35	50	10	0.81	<1	11	124	18	2.83	20	0.82	529	3	0.02	30	300	32	20	<20	59	0.02	<10	13	<10	<1	50
48	81770	0.2	1.09	35	60	15	1.19	2	15	103	34	3.49	20	1.05	643	5	0.01	38	400	46	35	<20	97	0.02	<10	12	<10	2	59
49	81771	0.2	1.07	25	55	10	0.68	<1	11	151	17	2.80	20	0.68	521	4	0.03	24	340	34	15	<20	35	0.01	<10	15	<10	1	49
50	81772	0.2	1.62	30	65	<5	3.48	2	24	194	58	4.66	10	2.63	887	8	0.03	56	1280	46	50	<20	435	0.03	<10	76	<10	<1	62
51	81773	0.5	1.08	40	60	5	1.32	<1	11	137	39	3.26	<10	0.89	577	4	0.02	33	350	32	30	<20	136	0.02	<10	14	<10	1	44
52	81774	0.3	1.44	50	50	10	1.02	2	18	82	39	4.15	<10	1.05	582	5	<0.01	42	370	30	30	<20	97	0.02	<10	15	<10	<1	60
53	81775	0.9	0.94	85	50	10	2.34	1	17	122	43	3.88	<10	1.12	839	5	0.01	36	300	24	30	<20	223	0.02	<10	12	<10	4	42
54	81776	1.7	1.09	110	60	25	1.76	2	19	120	65	4.28	<10	1.05	701	5	0.01	47	330	30	30	<20	180	0.02	<10	14	<10	3	57
55	81777	0.2	0.88	30	45	10	1.53	<1	13	83	13	2.81	10	0.79	550	4	0.02	29	330	26	25	<20	106	0.01	<10	14	<10	1	46
56	81778	0.3	0.44	35	35	<5	2.40	<1	14	99	23	3.06	<10	0.89	710	3	0.01	30	220	22	30	<20	163	0.02	<10	9	<10	2	45
57	81779	<0.2	0.67	30	55	10	1.10	<1	15	84	21	3.01	10	0.73	437	3	0.01	32	440	24	15	<20	74	0.02	<10	10	<10	2	49
58	81780	0.8	0.33	55	50	15	3.22	1	20	81	33	3.92	<10	1.15	826	4	<0.01	35	250	30	30	<20	258	0.02	<10	9	<10	3	65
59	81781	<0.2	0.19	50	25	10	4.09	<1	8	174	12	3.06	<10	1.22	954	2	0.02	18	370	20	25	<20	355	0.02	<10	8	<10	3	41
60	81782	0.6	0.31	45	35	5	3.55	<1	17	103	27	3.78	<10	1.16	908	2	0.01	30	390	24	20	<20	287	0.02	<10	8	<10	3	48
61	81783	0.6	1.28	50	55	15	2.09	1	22	83	34	4.37	<10	1.18	678	5	0.01	42	300	36	25	<20	143	0.02	<10	15	<10	1	61
62	81784	0.5	0.68	45	40	10	3.25	<1	16	98	26	3.51	<10	0.95	710	4	0.01	36	240	26	20	<20	196	0.02	<10	11	<10	2	58
63	81785	0.3	0.53	45	40	20	4.24	1	17	101	25	3.97	<10	1.28	899	5	0.01	35	240	36	30	<20	288	0.02	<10	10	<10	3	74
64	81786	0.3	0.48	70	30	<5	3.92	1	17	79	30	3.42	<10	1.02	726	4	<0.01	34	290	26	30	<20	251	0.02	<10	11	<10	5	51
65	81787	0.5	0.30	55	70	10	2.61	<1	16	96	22	3.00	<10	0.83	581	3	0.02	36	450	22	20	<20	217	0.02	<10	8	<10	5	36
66	81788	0.2	0.22	75	45	10	3.28	<1	18	117	11	2.73	<10	0.96	637	2	0.02	35	410	14	15	<20	294	0.02	<10	8	<10	7	25
67	81789	0.6	0.35	55	60	15	3.65	2	22	86	31	4.04	<10	1.26	859	5	0.02	45	370	22	35	<20	279	0.02	<10	8	<10	3	47
68	81790	0.3	0.30	60	55	10	4.05	<1	15	131	31	2.75	<10	0.91	948	3	0.01	24	290	20	20	<20	275	0.02	<10	8	<10	9	48
69	81791	0.5	0.27	50	55	10	2.55	1	17	125	37	3.20	<10	1.01	798	3	0.01	33	250	26	20	<20	213	0.02	<10	8	<10	4	40
70	81792	0.6	0.29	45	45	10	2.70	1	14	119	29	3.50	<10	1.10	854	3	0.01	29	220	30	15	<20	218	0.02	<10	8	<10	1	154

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
71	81793	0.2	0.50	55	40	5	1.99	<1	14	124	22	2.99	<10	0.92	640	4	0.02	33	310	22	35	<20	149	0.02	<10	10	<10	2	55
72	81794	<0.2	0.52	30	35	5	1.39	<1	10	98	28	2.66	<10	0.80	559	1	0.01	23	290	18	10	<20	117	0.02	<10	9	<10	2	42
73	81795	0.3	0.41	<5	45	<5	2.58	<1	14	113	26	3.24	<10	1.16	918	2	0.01	26	370	14	20	<20	238	0.02	<10	8	<10	<1	40
74	81796	0.7	0.32	55	45	<5	1.99	<1	20	83	35	3.41	<10	0.98	722	2	0.01	34	300	24	5	<20	197	0.02	<10	7	<10	3	64
75	81797	0.6	0.31	45	55	<5	1.77	<1	18	101	31	3.52	<10	0.99	616	3	0.01	33	290	24	15	<20	182	0.02	<10	6	<10	5	44
76	81798	0.4	0.42	25	55	15	1.62	<1	19	99	37	3.28	<10	1.00	609	1	0.01	31	390	24	<5	<20	150	0.02	<10	8	<10	3	44
77	81799	0.5	0.67	35	60	5	1.40	1	20	86	32	3.29	<10	1.02	531	4	<0.01	33	370	26	20	<20	133	0.02	<10	8	<10	3	53
78	81800	0.3	0.24	35	40	10	2.80	1	12	100	20	2.81	<10	1.01	929	2	0.01	22	280	20	25	<20	252	0.02	<10	5	<10	6	38
79	81801	<0.2	0.37	35	40	15	2.30	<1	9	120	14	2.48	<10	0.88	884	<1	0.02	16	260	16	<5	<20	194	0.02	<10	7	<10	4	35
80	81802	0.7	1.09	40	55	5	1.33	<1	19	113	33	3.98	<10	1.15	670	2	0.01	39	400	44	10	<20	122	0.03	<10	11	<10	2	73
81	81803	0.8	1.09	35	55	20	1.10	2	18	99	31	3.83	<10	1.17	634	7	0.01	37	310	38	35	<20	101	0.02	<10	12	<10	<1	58
82	81804	0.4	0.58	45	40	15	2.29	<1	13	90	27	3.24	<10	1.19	983	<1	0.01	25	280	38	5	<20	242	0.03	<10	8	<10	5	48
83	81805	0.4	1.05	35	50	15	1.65	<1	16	95	33	3.62	<10	1.24	758	3	0.01	34	300	38	10	<20	166	0.03	<10	13	<10	2	60
84	81806	0.5	0.55	35	55	10	2.35	<1	19	80	32	3.86	<10	1.28	855	2	0.02	39	370	22	15	<20	193	0.03	<10	9	<10	3	50
85	81807	1.0	0.25	85	55	25	2.05	2	24	79	36	4.12	<10	0.92	521	4	<0.01	46	290	34	25	<20	194	0.02	<10	5	<10	3	37
86	81808	1.0	0.24	75	45	10	2.99	3	19	85	34	3.64	<10	0.96	707	4	0.01	38	340	188	20	<20	252	0.02	<10	6	<10	5	247
87	81809	0.4	0.29	35	45	15	3.81	6	16	74	44	3.50	10	1.32	954	11	<0.01	40	400	22	85	<20	283	<0.01	<10	8	<10	6	37
88	81810	0.2	1.18	50	50	25	2.13	<1	20	122	30	3.90	20	1.42	757	2	0.01	55	730	48	10	<20	163	0.03	<10	18	<10	5	61
89	81811	<0.2	0.73	30	35	5	1.51	2	11	91	33	2.29	20	0.91	463	3	0.01	28	360	30	25	<20	125	0.01	<10	9	<10	3	34
90	81812	<0.2	0.63	25	25	10	0.77	3	8	74	13	1.79	20	0.59	295	8	0.01	23	270	28	50	<20	59	<0.01	<10	10	<10	3	32
91	81813	<0.2	1.20	45	50	10	0.63	<1	14	90	28	2.93	40	0.86	377	1	0.01	30	430	44	<5	<20	46	0.02	<10	11	<10	3	49
92	81814	<0.2	1.46	45	45	15	0.82	3	16	59	36	3.57	30	1.19	470	6	0.01	42	410	44	40	<20	57	0.02	<10	15	<10	2	62
93	81815	<0.2	1.02	30	50	15	0.49	<1	11	99	20	2.55	30	0.77	323	3	0.01	29	380	30	10	<20	32	0.01	<10	12	<10	3	49
94	81816	0.2	0.95	30	35	10	0.58	<1	11	78	14	2.33	20	0.72	333	3	0.01	26	330	30	10	<20	39	0.01	<10	12	<10	3	42
95	81817	<0.2	0.53	30	30	5	1.10	<1	9	91	15	2.11	20	0.66	564	<1	0.02	18	290	22	<5	<20	90	0.02	<10	8	<10	2	34
96	81818	0.2	0.96	40	60	5	1.09	<1	12	107	21	2.67	30	0.86	641	<1	0.02	29	330	50	<5	<20	93	0.02	<10	11	<10	2	45
97	81819	0.2	1.61	55	55	15	0.52	2	19	80	43	3.50	40	1.08	396	10	<0.01	47	440	56	40	<20	35	0.01	<10	16	<10	2	64

QC DATA:***Repeat:***

1	81722	<0.2	0.35	15	45	10	0.65	<1	5	97	8	1.44	30	0.34	341	3	0.02	10	450	18	10	<20	47	<0.01	<10	6	<10	4	23
10	81731	<0.2	0.25	40	45	5	2.41	<1	11	86	3	2.27	10	0.82	456	2	0.02	23	350	10	15	<20	162	0.01	<10	6	<10	3	12
19	81740	0.2	0.23	50	45	<5	1.29	1	11	108	15	2.91	<10	0.71	365	4	0.02	22	430	14	25	<20	129	0.01	<10	7	<10	2	31
36	81757	<0.2	0.28	30	60	<5	0.33	1	14	56	24	3.33	30	0.83	396	3	0.01	28	380	20	15	<20	13	0.01	<10	5	<10	1	66
45	81767	0.2	0.36	35	50	10	1.05	2	15	74	28	3.14	<10	0.85	716	5	0.02	32	250	28	35	<20	77	0.02	<10	8	<10	2	68
54	81776	2.2	1.08	120	50	10	1.76	1	19	117	65	4.30	<10	1.05	706	5	0.01	44	340	30	25	<20	178	0.03	<10	14	<10	4	58
71	81793	0.2	0.52	40	55	<5	1.97	<1	14	126	23	2.94	<10	0.95	632	3	0.02	27	310	18	35	<20	167	0.02	<10	8	<10	3	53
80	81802	0.5	1.12	45	55	10	1.35	1	19	112	33	4.04	<10	1.18	678	7	<0.01	44	410	44	45	<20	117	0.02	<10	12	<10	2	74
89	81811	0.2	0.73	30	35	<5	1.50	<1	11	92	35	2.28	20	0.90	458	3	<0.01	27	350	32	20	<20	123	0.01	<10	9	<10	2	33

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
Resplit:																													
1	81722	<0.2	0.38	25	50	5	0.61	<1	6	88	8	1.43	30	0.34	330	1	0.02	12	450	20	5	<20	41	0.02	<10	6	<10	3	23
36	81757	0.2	0.25	55	65	5	0.37	1	14	86	26	3.35	30	0.85	405	2	0.01	30	410	22	15	<20	14	0.02	<10	6	<10	2	65
71	81793	0.3	0.54	45	40	5	1.94	1	16	108	24	3.03	<10	0.98	624	9	0.01	32	300	20	45	<20	168	0.01	<10	9	<10	3	49
Standard:																													
Pb 129a		11.8	0.80	15	70	<5	0.44	55	6	11	1317	1.50	<10	0.69	329	3	0.02	10	470	6106	15	<20	30	0.03	<10	20	<10	<1	9923
Pb 129a		11.6	0.82	10	70	<5	0.44	55	7	11	1379	1.50	<10	0.70	330	3	0.02	7	470	6140	10	<20	29	0.04	<10	21	<10	<1	9961
Pb 129a		11.5	0.86	10	75	<5	0.45	55	6	11	1446	1.51	<10	0.71	334	3	0.02	7	450	6082	10	<20	32	0.12	<10	18	<10	<1	9947

ECO TECH LABORATORY LTD.

Jutta Jealouse

B.C. Certified Assayer

JJ/ndw
df/948s
XLS/07

CERTIFICATE OF ASSAY AK 2008-0963

Manson Creek Resources

20-Aug-08

Suite 500, 926 - 5 Avenue S.W.

Calgary, AB

T2P 0N7

No. of samples received: 81

Sample Type: Core

Project: Meridian

Submitted by: Dustin Rainer

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	81820	<0.03	<0.001
2	81821	<0.03	<0.001
3	81822	<0.03	<0.001
4	81823	<0.03	<0.001
5	81824	<0.03	<0.001
6	81825	<0.03	<0.001
7	81826	<0.03	<0.001
8	81827	<0.03	<0.001
9	81828	<0.03	<0.001
10	81829	<0.03	<0.001
11	81830	<0.03	<0.001
12	81831	<0.03	<0.001
13	81832	<0.03	<0.001
14	81833	<0.03	<0.001
15	81834	<0.03	<0.001
16	81835	<0.03	<0.001
17	81836	<0.03	<0.001
18	81837	<0.03	<0.001
19	81838	<0.03	<0.001
20	81839	<0.03	<0.001
21	81840	<0.03	<0.001
22	81841	<0.03	<0.001
23	81842	<0.03	<0.001
24	81843	<0.03	<0.001
25	81844	<0.03	<0.001

ECO TECH LABORATORY LTD.

Jutta Jealouse

B.C. Certified Assayer

ET #.	Tag #	Au (g/t)	Au (oz/t)
26	81845	<0.03	<0.001
27	81846	0.09	0.003
28	81847	<0.03	<0.001
29	81848	0.05	0.001
30	81849	<0.03	<0.001
31	81850	<0.03	<0.001
32	81851	<0.03	<0.001
33	81852	<0.03	<0.001
34	81853	<0.03	<0.001
35	81854	<0.03	<0.001
36	81855	<0.03	<0.001
37	81856	<0.03	<0.001
38	81857	<0.03	<0.001
39	81858	<0.03	<0.001
40	81859	<0.03	<0.001
41	81860	<0.03	<0.001
42	81861	<0.03	<0.001
43	81862	<0.03	<0.001
44	81863	<0.03	<0.001
45	81864	0.05	0.001
46	81865	<0.03	<0.001
47	81866	<0.03	<0.001
48	81867	0.07	0.002
49	81868	<0.03	<0.001
50	81869	<0.03	<0.001
51	81870	<0.03	<0.001
52	81871	<0.03	<0.001
53	81872	<0.03	<0.001
54	81873	<0.03	<0.001
55	81874	<0.03	<0.001
56	81875	<0.03	<0.001
57	81876	<0.03	<0.001
58	81877	<0.03	<0.001
59	81878	<0.03	<0.001
60	81879	<0.03	<0.001
61	81880	<0.03	<0.001
62	81881	<0.03	<0.001
63	81882	<0.03	<0.001
64	81883	<0.03	<0.001
65	81884	<0.03	<0.001

ECO TECH LABORATORY LTD.

Jutta Jealouse

B.C. Certified Assayer

ET #.	Tag #	Au (g/t)	Au (oz/t)
66	81885	<0.03	<0.001
67	81886	<0.03	<0.001
68	81887	<0.03	<0.001
69	81888	<0.03	<0.001
70	81889	<0.03	<0.001
71	81890	<0.03	<0.001
72	81891	<0.03	<0.001
73	81892	<0.03	<0.001
74	81893	<0.03	<0.001
75	81894	<0.03	<0.001
76	81895	<0.03	<0.001
77	81896	<0.03	<0.001
78	81897	<0.03	<0.001
79	81898	<0.03	<0.001
80	81899	<0.03	<0.001
81	81900	<0.03	<0.001

QC DATA:

Repeat:

1	81820	<0.03	<0.001
10	81829	<0.03	<0.001
19	81838	<0.03	<0.001
36	81855	<0.03	<0.001
45	81864	<0.03	<0.001
54	81873	<0.03	<0.001
71	81890	<0.03	<0.001

Resplit

1	81820	<0.03	<0.001
36	81855	<0.03	<0.001
71	81890	<0.03	<0.001

Standard:

OXI57	1.83	0.053
OXI57	1.83	0.053
OXI57	1.81	0.053

JJ/ap
XLS/07

ECO TECH LABORATORY LTD.

Jutta Jealouse
B.C. Certified Assayer

ECO TECH LABORATORY LTD.

10041 Dallas Drive

KAMLOOPS, B.C.

V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 2008- 0963

Manson Creek Resources

Suite 500, 926 - 5 Avenue S.W.

Calgary, AB

T2P 0N7

Phone: 250-573-5700

Fax : 250-573-4557

No. of samples received: 81

Sample Type: Core

Project: Meridian

Submitted by: Dustin Rainer

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	81820	<0.2	1.04	10	45	5	0.56	<1	10	65	19	2.49	20	0.52	385	2	0.01	21	510	44	<5	<20	64	0.02	<10	8	<10	<1	60
2	81821	<0.2	1.13	5	50	<5	0.59	<1	12	63	32	2.68	20	0.56	410	2	0.01	24	590	38	5	<20	48	0.02	<10	9	<10	<1	58
3	81822	<0.2	1.13	<5	45	5	0.39	<1	11	51	23	2.67	10	0.54	340	1	<0.01	23	520	38	<5	<20	32	0.02	<10	8	<10	1	54
4	81823	<0.2	1.39	<5	55	5	0.28	<1	13	66	28	3.34	20	0.62	344	4	<0.01	31	500	44	15	<20	17	0.02	<10	10	<10	1	61
5	81824	<0.2	1.02	10	50	<5	0.49	<1	10	45	21	2.43	20	0.49	358	2	0.01	24	500	34	<5	<20	27	0.02	<10	7	<10	2	52
6	81825	<0.2	0.84	10	40	5	0.98	<1	8	78	15	2.09	20	0.40	537	<1	0.01	18	440	50	<5	<20	126	0.02	<10	6	<10	<1	39
7	81826	<0.2	1.13	5	60	10	0.54	<1	12	52	22	2.73	20	0.53	446	2	0.01	27	650	46	10	<20	13	0.02	<10	9	<10	2	55
8	81827	<0.2	0.88	10	55	<5	0.68	<1	10	67	18	2.37	20	0.43	388	1	0.01	20	530	36	<5	<20	20	0.02	<10	7	<10	2	41
9	81828	<0.2	1.00	15	50	<5	0.44	<1	10	63	16	2.48	20	0.46	415	1	0.01	21	570	54	<5	<20	41	0.02	<10	9	<10	1	49
10	81829	<0.2	1.27	10	60	<5	0.16	<1	13	60	21	3.03	20	0.58	453	2	<0.01	28	620	44	<5	<20	2	0.02	<10	10	<10	2	56
11	81830	<0.2	1.21	5	55	<5	0.85	<1	14	51	35	3.16	20	0.72	722	4	<0.01	29	540	72	20	<20	84	0.02	<10	10	<10	3	66
12	81831	<0.2	1.29	10	60	10	0.48	1	13	57	24	3.02	20	0.72	395	3	0.01	29	580	50	15	<20	50	0.03	<10	10	<10	2	63
13	81832	<0.2	0.96	20	50	<5	0.66	<1	10	62	15	2.38	20	0.59	380	2	0.02	23	600	40	<5	<20	61	0.02	<10	9	<10	1	51
14	81833	<0.2	1.01	10	50	<5	0.38	<1	10	72	18	2.45	20	0.50	327	1	0.02	24	560	38	<5	<20	18	0.02	<10	10	<10	<1	46
15	81834	0.2	0.99	<5	40	<5	0.55	<1	11	68	20	2.44	20	0.54	379	12	0.01	25	510	38	10	<20	39	0.02	<10	8	<10	<1	48
16	81835	<0.2	0.21	<5	40	5	0.62	<1	8	71	13	2.10	20	0.42	401	<1	0.02	14	500	10	<5	<20	38	0.02	<10	3	<10	1	46
17	81836	<0.2	0.20	<5	55	10	0.50	<1	10	64	19	2.47	20	0.29	491	1	0.01	16	520	6	<5	<20	36	0.02	<10	2	<10	<1	19
18	81837	<0.2	0.21	5	50	5	0.81	<1	10	69	15	2.74	10	0.64	514	<1	0.02	17	550	6	<5	<20	58	0.03	<10	3	<10	1	27
19	81838	<0.2	0.22	10	45	5	0.76	1	12	50	22	3.16	10	0.68	589	2	0.02	20	510	6	10	<20	51	0.02	<10	3	<10	<1	26
20	81839	<0.2	0.21	15	50	5	0.65	<1	12	70	21	2.71	20	0.64	410	<1	0.01	18	510	8	<5	<20	39	0.02	<10	3	<10	<1	33
21	81840	<0.2	0.23	10	55	<5	0.49	1	13	50	32	3.30	20	0.72	507	2	0.01	21	490	10	<5	<20	20	0.03	<10	3	<10	<1	50
22	81841	<0.2	0.19	<5	45	<5	1.58	<1	11	55	33	3.23	20	0.83	690	1	0.02	17	480	6	10	<20	97	0.03	<10	3	<10	3	22
23	81842	0.4	0.19	40	45	10	1.38	<1	26	63	32	3.88	<10	0.59	510	3	<0.01	41	480	14	10	<20	133	0.03	<10	2	<10	<1	27
24	81843	<0.2	0.20	15	45	<5	0.53	<1	13	76	20	3.26	10	0.52	562	2	0.02	18	410	6	5	<20	38	0.02	<10	3	<10	<1	72
25	81844	<0.2	0.22	15	45	<5	0.49	<1	15	56	25	3.17	10	0.56	526	2	0.01	22	330	8	10	<20	30	0.02	<10	3	<10	<1	47
26	81845	0.2	0.24	<5	55	<5	0.92	<1	11	61	22	3.08	<10	0.67	442	2	0.02	20	560	180	5	<20	68	0.02	<10	3	<10	<1	53
27	81846	0.2	0.20	<5	45	<5	1.46	<1	10	72	22	2.69	<10	0.63	554	<1	0.02	16	410	26	<5	<20	111	0.03	<10	2	<10	1	43
28	81847	<0.2	0.24	<5	45	10	1.60	<1	12	43	20	3.37	20	0.86	832	2	0.02	19	460	18	10	<20	90	0.03	<10	2	<10	<1	57
29	81848	<0.2	0.22	15	50	<5	0.90	<1	11	62	14	2.84	<10	0.66	392	<1	0.02	18	340	10	<5	<20	67	0.02	<10	3	<10	<1	34
30	81849	<0.2	0.21	40	45	5	0.79	<1	15	67	21	3.49	<10	0.83	439	2	0.01	24	460	14	<5	<20	68	0.03	<10	4	<10	<1	30

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
31	81850	<0.2	0.32	195	40	15	5.57	<1	35	52	3	5.22	<10	2.75	1083	<1	0.02	121	820	8	10	<20	554	0.05	<10	19	<10	2	36
32	81851	0.2	0.84	190	30	10	7.06	1	44	210	49	6.80	<10	4.99	1273	3	0.02	213	880	16	30	<20	699	0.06	<10	58	<10	<1	47
33	81852	<0.2	2.21	45	15	15	6.55	4	51	408	69	6.85	<10	5.54	1268	8	0.02	265	860	52	50	<20	695	0.10	<10	162	<10	<1	96
34	81853	<0.2	3.22	15	30	20	6.59	<1	50	341	93	6.66	<10	4.54	1260	5	0.02	203	940	58	35	<20	671	0.25	<10	205	<10	<1	107
35	81854	<0.2	2.37	5	310	25	4.67	5	54	303	85	7.03	<10	3.52	1163	10	0.03	195	1610	42	70	<20	480	0.23	<10	166	<10	<1	167
36	81855	0.4	2.27	<5	60	5	5.04	1	55	362	95	8.29	<10	2.90	1200	5	0.03	187	1310	48	50	<20	298	0.17	<10	175	<10	<1	103
37	81856	<0.2	2.45	<5	185	20	5.02	2	56	367	82	7.14	<10	3.52	1197	5	0.03	181	1180	42	40	<20	456	0.28	<10	189	<10	<1	88
38	81857	<0.2	1.69	20	65	20	1.80	9	25	126	31	4.89	<10	1.44	906	13	0.01	64	960	180	35	<20	97	0.04	<10	38	<10	<1	1275
39	81858	<0.2	1.09	10	55	10	1.17	1	14	58	19	3.37	<10	0.71	565	3	<0.01	27	420	32	15	<20	55	0.03	<10	9	<10	<1	42
40	81859	<0.2	1.24	10	60	<5	0.39	<1	11	73	22	2.87	20	0.56	300	3	0.01	24	380	30	20	<20	1	0.02	<10	9	<10	<1	42
41	81860	<0.2	0.33	10	40	<5	0.55	<1	11	78	17	2.89	10	0.70	331	2	0.01	23	390	10	5	<20	21	0.02	<10	4	<10	2	45
42	81861	0.6	0.24	25	35	<5	1.66	<1	18	74	35	3.44	<10	0.56	477	2	0.01	34	450	16	5	<20	102	0.03	<10	4	<10	<1	31
43	81862	0.5	0.25	20	35	5	2.33	2	13	92	40	3.48	<10	0.83	647	4	0.01	28	420	24	20	<20	156	0.02	<10	4	<10	1	33
44	81863	0.5	0.20	25	35	10	2.38	<1	12	76	20	2.92	<10	0.64	640	<1	<0.01	21	440	16	<5	<20	144	0.04	<10	3	<10	1	18
45	81864	0.2	0.20	20	45	<5	1.28	<1	10	71	21	2.39	<10	0.52	411	2	0.01	21	370	10	<5	<20	76	0.02	<10	3	<10	<1	21
46	81865	<0.2	0.15	10	25	<5	1.81	<1	6	102	5	2.10	<10	0.65	421	<1	0.01	12	230	6	5	<20	145	0.02	<10	2	<10	3	19
47	81866	<0.2	0.20	15	35	<5	1.48	<1	8	103	10	1.93	<10	0.54	395	<1	0.01	12	320	6	<5	<20	107	0.02	<10	3	<10	1	13
48	81867	<0.2	0.19	50	40	10	1.79	<1	10	81	23	2.73	<10	0.62	508	<1	0.01	21	320	12	<5	<20	134	0.03	<10	3	<10	<1	29
49	81868	<0.2	0.23	75	45	10	0.79	6	17	68	23	3.80	20	0.78	491	7	0.01	34	440	18	15	<20	45	0.03	<10	3	<10	<1	981
50	81869	<0.2	0.23	30	45	<5	0.72	3	15	65	26	3.49	20	0.83	512	4	0.01	32	450	22	10	<20	44	0.03	<10	3	<10	<1	217
51	81870	0.2	0.28	30	40	5	0.71	<1	11	94	26	2.81	10	0.64	445	<1	0.02	25	350	16	<5	<20	52	0.03	<10	3	<10	<1	48
52	81871	0.3	0.84	20	40	5	0.46	2	16	56	27	3.73	20	0.87	494	3	0.02	36	500	38	15	<20	15	0.02	<10	8	<10	<1	72
53	81872	0.2	1.26	30	45	<5	0.78	<1	13	65	27	3.25	20	0.82	576	5	0.01	33	510	40	20	<20	56	0.02	<10	12	<10	<1	62
54	81873	<0.2	1.40	20	45	10	0.68	<1	14	67	22	3.53	20	0.88	574	3	0.02	33	480	48	10	<20	50	0.03	<10	13	<10	<1	65
55	81874	<0.2	1.18	20	45	<5	0.85	<1	13	80	23	3.14	20	0.78	632	<1	0.02	30	470	44	<5	<20	71	0.03	<10	11	<10	<1	59
56	81875	<0.2	1.67	15	55	10	0.37	1	16	59	27	3.88	20	0.91	377	4	0.01	40	510	48	20	<20	10	0.03	<10	14	<10	<1	124
57	81876	<0.2	1.29	10	45	10	0.47	2	15	85	24	3.34	20	0.74	402	3	0.01	35	480	52	15	<20	18	0.02	<10	11	<10	<1	134
58	81877	<0.2	1.09	10	30	<5	0.71	<1	11	98	12	2.62	<10	0.73	455	<1	0.02	19	420	34	<5	<20	49	0.02	<10	17	<10	<1	444
59	81878	<0.2	2.73	75	20	15	6.26	2	42	394	29	5.69	<10	5.53	1346	9	<0.01	272	1300	56	60	<20	554	0.05	<10	68	<10	<1	89
60	81879	<0.2	1.57	5	55	<5	0.71	14	17	83	31	3.55	<10	1.01	468	15	0.01	39	430	66	15	<20	44	0.03	<10	17	<10	<1	2254
61	81880	<0.2	1.50	<5	55	10	0.62	1	17	76	31	3.56	<10	0.91	515	5	0.01	40	450	46	20	<20	49	0.03	<10	14	<10	<1	70
62	81881	<0.2	1.04	<5	40	10	0.99	<1	11	68	15	2.70	10	0.78	564	<1	0.02	27	400	34	<5	<20	85	0.03	<10	11	<10	<1	47
63	81882	<0.2	2.10	5	50	10	0.20	3	19	77	37	4.57	20	1.17	270	8	<0.01	50	460	50	45	<20	6	0.03	<10	19	<10	<1	85
64	81883	0.2	0.69	<5	45	<5	1.31	<1	9	114	32	2.37	10	0.71	799	<1	0.02	23	330	122	<5	<20	170	0.02	<10	8	<10	2	35
65	81884	<0.2	1.38	15	50	<5	0.52	<1	14	71	27	3.14	20	0.84	468	<1	0.01	33	450	38	<5	<20	30	0.03	<10	13	<10	<1	63
66	81885	<0.2	1.93	15	60	<5	0.35	<1	18	71	34	4.15	20	1.10	505	2	0.01	44	500	56	<5	<20	22	0.03	<10	17	<10	<1	77
67	81886	<0.2	2.10	10	55	10	0.31	<1	20	70	35	4.59	20	1.20	422	4	<0.01	48	480	58	15	<20	15	0.03	<10	18	<10	<1	85
68	81887	<0.2	1.74	15	60	<5	0.38	<1	16	61	31	3.87	20	0.96	476	3	0.01	40	500	52	15	<20	21	0.03	<10	14	<10	<1	75
69	81888	<0.2	1.73	15	65	10	0.32	1	17	67	30	3.85	20	0.93	463	3	0.01	39	520	56	15	<20	14	0.03	<10	15	<10	<1	86
70	81889	<0.2	1.38	20	60	<5	0.50	<1	13	85	29	3.18	20	0.77	605	<1	0.02	26	460	64	<5	<20	30	0.04	<10	14	<10	<1	68

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
71	81890	<0.2	1.77	20	55	15	0.23	<1	16	77	30	3.84	20	0.96	417	2	0.01	39	520	56	10	<20	<1	0.03	<10	16	<10	<1	74
72	81891	<0.2	1.85	15	70	10	0.15	1	17	65	33	3.95	20	1.04	362	6	0.02	41	510	56	20	<20	9	0.06	<10	17	<10	<1	76
73	81892	<0.2	0.88	15	80	5	0.57	<1	11	117	16	2.50	<10	0.76	448	<1	0.07	19	400	34	<5	<20	55	0.17	<10	40	<10	<1	34
74	81893	<0.2	3.44	35	25	20	4.71	2	42	510	35	5.30	<10	5.07	909	11	0.02	232	1850	66	65	<20	616	0.29	<10	123	<10	<1	60
75	81894	<0.2	3.23	45	15	15	5.87	<1	41	498	45	5.06	<10	4.66	1062	6	0.02	227	1930	62	35	<20	645	0.34	<10	117	<10	<1	72
76	81895	<0.2	2.90	45	20	15	4.18	<1	38	494	37	4.52	<10	4.28	755	6	0.02	211	1910	58	35	<20	499	0.30	<10	105	<10	<1	48
77	81896	<0.2	2.86	45	25	10	4.69	1	37	486	33	4.42	<10	4.21	754	8	0.02	217	1590	54	60	<20	626	0.25	<10	103	<10	<1	46
78	81897	<0.2	1.08	20	40	<5	0.91	<1	11	124	36	2.50	<10	0.80	568	1	0.04	24	390	48	<5	<20	80	0.07	<10	35	<10	<1	75
79	81898	<0.2	1.61	20	60	<5	0.51	<1	16	74	28	3.63	20	0.96	568	2	0.02	38	470	52	<5	<20	27	0.03	<10	17	<10	<1	73
80	81899	0.5	1.62	25	70	5	1.27	<1	18	84	28	4.22	10	1.13	1077	2	0.02	44	510	172	15	<20	157	0.04	<10	16	<10	<1	95
81	81900	<0.2	1.64	30	55	10	0.40	<1	16	60	25	3.84	10	0.84	440	3	0.02	37	530	46	10	<20	28	0.03	<10	15	<10	<1	75

QC DATA:**Repeat:**

1	81820	<0.2	1.04	5	45	5	0.55	<1	10	64	18	2.47	20	0.52	383	2	0.01	21	510	44	<5	<20	58	0.02	<10	8	<10	<1	58
10	81829	<0.2	1.23	20	55	<5	0.15	<1	12	59	21	2.94	20	0.56	441	3	<0.01	28	600	42	5	<20	3	0.02	<10	10	<10	1	55
19	81838	0.2	0.21	10	50	<5	0.76	<1	12	50	21	3.15	10	0.68	589	2	0.02	20	510	6	<5	<20	50	0.02	<10	3	<10	<1	27
36	81855	0.4	2.26	5	55	10	5.02	3	55	360	94	8.25	<10	2.92	1194	12	0.03	191	1300	46	65	<20	301	0.17	<10	175	<10	<1	105
45	81864	0.2	0.19	20	45	10	1.28	<1	10	71	21	2.41	<10	0.53	415	<1	0.01	21	360	10	<5	<20	90	0.02	<10	3	<10	<1	22
54	81873	<0.2	1.41	20	50	10	0.68	<1	15	67	23	3.56	20	0.89	581	<1	0.02	32	480	52	<5	<20	53	0.03	<10	13	<10	<1	66
71	81890	<0.2	1.79	10	60	10	0.24	<1	17	76	30	3.89	20	0.98	424	3	0.01	40	520	56	15	<20	<1	0.03	<10	16	<10	<1	74

Resplit:

1	81820	0.2	1.10	10	50	10	0.53	<1	11	58	19	2.56	20	0.54	376	<1	0.01	23	530	46	<5	<20	59	0.02	<10	9	<10	1	62
36	81855	0.5	2.32	<5	60	10	5.08	5	57	372	88	8.46	<10	3.01	1206	3	0.03	198	1310	48	50	<20	314	0.19	<10	179	<10	<1	102
71	81890	0.2	1.84	20	70	10	0.25	2	17	75	28	3.95	30	1.00	438	<1	0.02	43	530	60	20	<20	1	0.04	<10	17	<10	<1	75

Standard:

Pb129a		11.9	0.81	15	65	<5	0.46	57	6	10	1353	1.56	<10	0.68	374	5	0.03	9	450	6208	15	<20	33	0.03	<10	19	<10	<1	9985
Pb129a		11.6	0.79	10	60	<5	0.45	56	6	11	1338	1.55	<10	0.66	370	3	0.03	9	450	6208	15	<20	29	0.03	<10	18	<10	<1	9955
Pb129a		11.7	0.83	15	65	<5	0.48	55	6	11	1350	1.59	<10	0.67	381	3	0.03	10	450	6140	15	<20	30	0.03	<10	18	<10	<1	9946

JJ/nw
df/961s
XLS/07

ECO TECH LABORATORY LTD.

Jutta Jealouse

B.C. Certified Assayer

CERTIFICATE OF ASSAY AK 2008- 0994

Manson Creek Resources
Suite 500, 926 - 5 Avenue S.W.
Calgary, AB
T2P 0N7

02-Sep-08

No. of samples received: 75
Sample Type: Core
Project: Maridian
Submitted by: Stephen Rowins

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	81501	3.65	0.106
2	81502	<0.03	<0.001
3	81503	<0.03	<0.001
4	81504	<0.03	<0.001
5	81505	<0.03	<0.001
6	81506	<0.03	<0.001
7	81507	<0.03	<0.001
8	81508	<0.03	<0.001
9	81510	<0.03	<0.001
10	81511	<0.03	<0.001
11	81512	<0.03	<0.001
12	81513	<0.03	<0.001
13	81514	<0.03	<0.001
14	81515	<0.03	<0.001
15	81516	<0.03	<0.001
16	81517	<0.03	<0.001
17	81518	<0.03	<0.001
18	81519	<0.03	<0.001
19	81520	<0.03	<0.001
20	81521	<0.03	<0.001
21	81522	<0.03	<0.001
22	81523	<0.03	<0.001
23	81524	<0.03	<0.001
24	81525	<0.03	<0.001
25	81526	<0.03	<0.001
26	81527	<0.03	<0.001
27	81528	<0.03	<0.001
28	81529	<0.03	<0.001
29	81530	<0.03	<0.001

ECO TECH LABORATORY LTD.

Jutta Jealous
B.C. Certified Assayer

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	81531	1.34	0.039
31	81532	0.28	0.008
32	81533	1.50	0.044
33	81534	0.70	0.020
34	81535	0.84	0.024
35	81536	0.40	0.012
36	81537	0.14	0.004
37	81538	0.06	0.002
38	81539	0.26	0.008
39	81540	<0.03	<0.001
40	81541	<0.03	<0.001
41	81542	<0.03	<0.001
42	81543	<0.03	<0.001
43	81544	0.28	0.008
44	81545	1.03	0.030
45	81546	0.32	0.009
46	81547	0.09	0.003
47	81548	0.03	0.001
48	81549	2.46	0.072
49	81550	1.14	0.033
50	81551	<0.03	<0.001
51	81552	<0.03	<0.001
52	81553	<0.03	<0.001
53	81554	0.06	0.002
54	81555	0.26	0.008
55	81556	0.50	0.015
56	81557	<0.03	<0.001
57	81558	<0.03	<0.001
58	81559	<0.03	<0.001
59	81560	0.03	0.001
60	81561	<0.03	<0.001
61	81562	<0.03	<0.001
62	81563	<0.03	<0.001
63	81564	<0.03	<0.001
64	81565	<0.03	<0.001
65	81566	<0.03	<0.001
66	81567	<0.03	<0.001
67	81568	<0.03	<0.001
68	81569	0.40	0.012
69	81570	<0.03	<0.001
70	81571	<0.03	<0.001
71	81572	0.07	0.002
72	81573	<0.03	<0.001
73	81574	<0.03	<0.001
74	81575	<0.03	<0.001
75	81576	<0.03	<0.001

ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

ET #.	Tag #	Au (g/t)	Au (oz/t)
QC DATA:			
Repeat:			
1	81501	<0.03	<0.001
10	81511	<0.03	<0.001
19	81520	<0.03	<0.001
30	81531	1.28	0.037
32	81533	1.39	0.041
34	81535	0.75	0.022
36	81537	0.18	0.005
44	81545	0.92	0.027
45	81546	0.36	0.010
48	81549	2.40	0.070
49	81550	1.10	0.032
54	81555	0.30	0.009
68	81569	0.46	0.013
71	81572	0.08	0.002
Resplit:			
36	81537	0.16	0.005
71	81572	0.08	0.002
Standard:			
	Ox167	1.86	0.054
	Ox167	1.84	0.054
	Ox167	1.79	0.052

JJ/kk
XLS/08

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

ECO TECH LABORATORY LTD.

10041 Dallas Drive

KAMLOOPS, B.C.

V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 2008- 0994

Manson Creek Resources

Suite 500, 926 - 5 Avenue S.W.

Calgary, AB

T2P 0N7

Phone: 250-573-5700

Fax : 250-573-4557

No. of samples received: 75

Sample Type: Core

Project: Maridian

Submitted by: Stephen Rowins

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	81501	<0.2	1.42	15	45	5	2.81	<1	15	94	23	3.36	<10	0.74	409	<1	0.01	30	740	32	<5	<20	190	0.01	<10	14	<10	<1	67
2	81502	<0.2	1.19	30	25	5	7.24	<1	11	119	26	2.98	<10	0.68	804	<1	0.01	24	640	32	<5	<20	587	0.02	<10	13	<10	3	56
3	81503	<0.2	0.86	15	30	<5	1.58	<1	9	151	24	2.33	<10	0.53	521	<1	0.01	20	300	24	<5	<20	103	0.01	<10	9	<10	1	37
4	81504	0.2	0.59	20	45	<5	0.81	<1	14	151	36	2.84	<10	0.31	531	<1	0.01	30	430	42	<5	<20	53	0.01	<10	7	<10	2	45
5	81505	<0.2	1.02	20	40	<5	5.62	<1	13	141	27	3.03	<10	0.58	500	<1	0.02	26	450	34	<5	<20	439	0.02	<10	11	<10	<1	59
6	81506	<0.2	1.50	30	60	<5	0.67	<1	16	150	33	3.65	<10	0.80	372	1	0.02	34	560	44	<5	<20	47	0.01	<10	15	<10	<1	64
7	81507	<0.2	1.43	25	45	10	1.04	<1	17	111	31	3.75	<10	0.90	478	<1	0.02	34	620	44	<5	<20	59	0.02	<10	14	<10	<1	65
8	81508	<0.2	1.55	25	50	<5	3.01	2	21	149	37	4.46	<10	1.35	915	3	0.02	47	810	44	5	<20	360	0.02	<10	24	<10	1	75
9	81510	<0.2	1.05	10	60	<5	0.69	<1	13	124	28	3.04	<10	0.63	567	<1	0.02	26	400	34	<5	<20	48	0.01	<10	9	<10	<1	50
10	81511	<0.2	1.04	20	50	<5	1.27	<1	12	114	23	2.77	<10	0.72	472	<1	0.03	23	470	26	<5	<20	74	0.01	<10	10	<10	<1	49
11	81512	<0.2	0.42	20	35	5	2.75	1	7	158	17	2.44	<10	0.77	858	<1	0.02	17	210	12	<5	<20	169	0.01	<10	7	<10	1	27
12	81513	0.2	0.49	10	60	5	1.06	1	19	117	51	3.77	<10	0.70	580	<1	0.02	35	430	32	<5	<20	96	0.02	<10	7	<10	<1	70
13	81514	0.3	0.81	20	50	5	1.04	1	17	101	48	3.63	<10	0.69	533	2	0.02	35	450	36	<5	<20	88	0.02	<10	8	<10	<1	81
14	81515	<0.2	0.64	20	55	<5	1.67	1	17	116	38	3.15	<10	0.75	758	<1	0.02	29	530	32	<5	<20	144	0.01	<10	7	<10	<1	61
15	81516	<0.2	0.39	5	50	10	1.38	<1	10	128	16	2.51	10	0.68	530	<1	0.03	16	510	24	<5	<20	130	0.01	<10	5	<10	1	41
16	81517	<0.2	0.75	20	80	5	0.69	2	14	128	31	3.50	20	0.80	479	<1	0.03	28	610	32	<5	<20	58	0.01	<10	8	<10	<1	65
17	81518	<0.2	0.39	10	65	<5	1.56	<1	10	110	12	2.59	20	0.40	587	<1	0.02	13	610	14	<5	<20	73	0.02	<10	5	<10	3	28
18	81519	<0.2	0.59	10	75	10	0.81	1	12	124	18	3.16	20	0.58	553	<1	0.03	22	580	18	<5	<20	45	0.01	<10	6	<10	<1	40
19	81520	<0.2	0.55	20	65	<5	0.79	<1	11	136	28	3.13	30	0.59	511	<1	0.02	24	580	14	<5	<20	50	0.01	<10	6	<10	1	40
20	81521	<0.2	0.57	35	85	<5	0.60	<1	11	117	32	2.63	30	0.42	431	<1	0.02	18	620	16	<5	<20	40	0.01	<10	6	<10	<1	31
21	81522	0.2	1.55	20	85	10	0.59	2	17	89	42	3.75	30	0.87	480	2	0.01	38	630	46	<5	<20	43	0.01	<10	13	<10	<1	76
22	81523	<0.2	0.69	30	55	5	0.80	<1	10	130	18	2.54	20	0.60	494	<1	0.03	21	580	22	<5	<20	65	0.01	<10	8	<10	<1	35
23	81524	<0.2	1.19	35	65	<5	0.67	<1	14	114	36	3.04	20	0.73	468	<1	0.03	27	630	38	<5	<20	48	0.01	<10	12	<10	1	56
24	81525	<0.2	0.90	45	95	10	0.66	1	15	110	28	3.59	30	0.81	470	<1	0.02	31	620	26	<5	<20	45	0.01	<10	8	<10	<1	65
25	81526	<0.2	0.60	60	75	<5	0.44	2	15	72	19	3.87	30	0.87	421	<1	0.02	31	590	18	<5	<20	18	0.02	<10	6	<10	<1	62

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	81527	<0.2	0.43	45	75	10	0.71	1	11	98	22	3.13	20	0.69	428	<1	0.02	22	550	14	<5	<20	43	0.01	<10	5	<10	<1	45
27	81528	<0.2	0.34	30	70	<5	0.90	1	14	67	21	3.48	20	0.72	553	<1	0.02	22	510	12	<5	<20	59	0.02	<10	4	<10	<1	52
28	81529	<0.2	0.23	15	35	<5	1.35	<1	5	193	10	1.64	10	0.40	627	<1	0.06	7	220	14	<5	<20	90	0.01	<10	4	<10	<1	16
29	81530	0.2	0.38	55	70	5	1.41	2	14	92	22	3.49	10	0.80	588	<1	0.03	27	420	18	<5	<20	126	0.02	<10	6	<10	<1	49
30	81531	1.2	0.44	70	85	5	0.43	<1	12	180	24	3.15	<10	0.15	593	<1	0.04	23	480	18	<5	<20	40	0.02	<10	6	<10	1	34
31	81532	<0.2	0.38	55	70	15	0.68	2	13	119	4	4.70	10	0.41	338	<1	0.02	31	400	12	<5	<20	55	0.02	<10	6	<10	<1	34
32	81533	0.4	0.54	115	80	5	1.16	2	12	117	6	3.82	<10	0.32	540	<1	0.03	31	920	20	<5	<20	88	0.01	<10	8	<10	3	26
33	81534	1.0	0.21	55	35	5	1.16	<1	9	194	8	2.53	<10	0.35	279	<1	0.03	22	370	54	<5	<20	105	0.01	<10	5	<10	1	34
34	81535	1.4	0.21	265	45	20	0.86	4	14	197	16	6.94	<10	0.23	183	4	0.02	29	290	98	<5	<20	72	0.02	<10	4	<10	<1	22
35	81536	1.1	0.23	80	45	15	2.42	2	12	163	8	3.68	<10	0.72	525	<1	0.02	26	360	186	<5	<20	175	0.02	<10	5	<10	<1	29
36	81537	0.6	0.35	45	60	10	3.07	1	15	149	19	3.14	<10	0.85	632	<1	0.02	31	450	26	<5	<20	206	0.02	<10	7	<10	<1	29
37	81538	0.7	0.47	40	80	10	2.36	2	21	107	42	4.42	<10	1.33	548	<1	0.02	38	530	30	<5	<20	200	0.02	<10	8	<10	<1	51
38	81539	0.8	0.47	50	70	10	2.88	3	21	146	35	4.57	<10	1.14	533	1	0.02	45	390	32	5	<20	250	0.02	<10	8	<10	<1	111
39	81540	0.2	0.26	25	45	5	2.14	<1	9	148	9	2.16	<10	0.58	435	<1	0.03	19	330	20	<5	<20	134	0.01	<10	5	<10	<1	24
40	81541	<0.2	0.33	50	55	5	2.13	1	11	183	12	3.20	<10	0.78	543	<1	0.02	27	430	20	<5	<20	161	0.01	<10	6	<10	1	33
41	81542	<0.2	0.37	50	65	<5	1.19	1	12	130	10	2.18	10	0.59	335	<1	0.02	26	350	14	<5	<20	107	<0.01	<10	6	<10	<1	18
42	81543	<0.2	0.45	45	80	<5	1.21	<1	11	172	5	1.14	10	0.37	236	<1	0.03	19	370	12	<5	<20	104	<0.01	<10	7	<10	2	9
43	81544	0.3	0.33	95	65	10	1.63	1	12	155	23	2.51	<10	0.67	448	<1	0.02	26	560	20	<5	<20	170	0.01	<10	6	<10	4	22
44	81545	0.7	0.45	55	65	5	0.66	1	16	144	21	3.74	<10	0.68	302	<1	0.02	31	340	18	<5	<20	57	0.01	<10	6	<10	<1	34
45	81546	0.5	0.37	40	65	10	0.95	1	12	167	15	3.11	<10	0.74	329	<1	0.02	23	270	44	<5	<20	98	0.01	<10	6	<10	<1	39
46	81547	0.6	0.43	35	75	<5	0.36	1	17	103	25	3.98	<10	0.82	306	<1	0.02	33	420	18	<5	<20	27	0.02	<10	6	<10	<1	30
47	81548	0.4	0.40	35	65	<5	0.53	1	13	139	20	3.13	10	0.70	326	<1	0.02	26	380	14	<5	<20	40	0.01	<10	6	<10	<1	26
48	81549	1.1	0.30	85	45	5	0.70	<1	13	149	15	2.33	<10	0.41	216	<1	0.02	21	160	14	<5	<20	66	<0.01	<10	4	<10	<1	42
49	81550	1.0	0.31	60	55	<5	0.86	1	15	127	21	3.05	<10	0.58	259	<1	0.02	27	340	18	<5	<20	85	0.01	<10	5	<10	<1	30
50	81551	0.3	0.38	25	55	5	0.54	<1	14	134	27	3.17	<10	0.70	262	<1	0.03	25	380	24	<5	<20	33	0.01	<10	6	<10	<1	63
51	81552	0.4	0.35	20	55	10	0.96	2	14	136	24	3.35	<10	0.81	417	<1	0.03	27	340	14	<5	<20	60	0.01	<10	6	<10	<1	33
52	81553	0.2	0.19	10	25	5	0.48	<1	5	190	18	1.73	<10	0.34	211	<1	0.03	11	190	8	<5	<20	20	<0.01	<10	3	<10	<1	36
53	81554	0.2	0.34	25	60	5	0.91	<1	11	135	23	3.07	<10	0.74	362	<1	0.03	21	320	16	<5	<20	60	0.01	<10	5	<10	<1	40
54	81555	0.4	0.47	25	75	10	0.59	1	15	113	24	3.65	10	0.63	330	1	0.03	25	470	20	<5	<20	33	0.01	<10	6	<10	<1	43
55	81556	0.5	0.26	50	55	5	2.67	2	12	122	16	3.22	<10	0.92	595	<1	0.02	22	260	22	<5	<20	174	0.01	<10	5	<10	2	74
56	81557	<0.2	0.34	20	55	<5	0.88	1	9	186	13	2.68	10	0.62	339	<1	0.03	18	250	12	<5	<20	51	0.01	<10	5	<10	<1	32
57	81558	0.3	0.42	25	65	10	0.33	1	11	146	17	2.72	10	0.49	252	<1	0.03	20	320	14	<5	<20	8	<0.01	<10	5	<10	<1	27
58	81559	0.2	0.30	20	50	5	0.59	<1	7	235	14	2.25	<10	0.33	287	<1	0.03	14	280	12	<5	<20	28	0.01	<10	4	<10	1	26
59	81560	0.4	0.50	35	75	10	0.16	1	19	62	30	4.26	20	0.74	207	<1	0.03	33	570	18	<5	<20	<1	0.02	<10	6	<10	<1	47
60	81561	0.3	0.40	20	75	10	0.29	2	12	194	17	4.37	<10	0.15	452	1	0.03	28	380	16	<5	<20	11	0.01	<10	6	<10	<1	29
61	81562	0.2	0.26	15	40	10	0.51	<1	7	129	6	1.91	<10	0.28	259	<1	0.02	13	240	10	<5	<20	24	<0.01	<10	3	<10	<1	24
62	81563	0.2	0.37	20	55	<5	0.44	<1	9	158	5	2.34	<10	0.33	240	<1	0.03	18	290	12	<5	<20	15	<0.01	<10	5	<10	<1	17
63	81564	0.3	0.26	20	45	<5	0.66	<1	10	169	10	2.25	<10	0.28	367	<1	0.03	14	230	8	<5	<20	45	0.01	<10	5	<10	<1	21
64	81565	0.2	0.50	20	70	5	0.52	3	15	103	26	4.48	10	0.98	403	3	0.04	31	440	26	10	<20	23	0.01	<10	6	<10	<1	48
65	81566	0.2	0.37	35	60	10	0.60	<1	17	124	10	3.15	<10	0.50	275	<1	0.03	26	330	16	<5	<20	30	0.01	<10	5	<10	<1	27

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
66	81567	0.3	0.55	35	75	<5	0.26	1	16	99	26	3.44	20	0.71	199	<1	0.04	28	410	20	<5	<20	3	0.01	<10	6	<10	<1	77
67	81568	0.3	0.28	20	45	5	0.20	<1	9	167	21	2.40	<10	0.16	206	<1	0.04	17	240	40	<5	<20	8	<0.01	<10	5	<10	<1	41
68	81569	0.2	0.35	25	65	5	0.15	<1	9	258	12	2.27	<10	0.17	280	<1	0.03	18	230	18	<5	<20	3	<0.01	<10	6	<10	<1	34
69	81570	0.3	0.38	15	65	<5	0.26	1	11	126	19	2.47	10	0.35	202	<1	0.03	19	340	16	<5	<20	9	<0.01	<10	5	<10	<1	23
70	81571	0.3	0.33	15	45	5	0.13	<1	8	166	20	2.25	<10	0.13	145	<1	0.03	14	270	14	<5	<20	<1	<0.01	<10	4	<10	<1	53
71	81572	0.4	0.60	38	93	11	0.56	2	26	77	41	4.67	<10	0.60	416	1	0.03	41	479	28	<5	<20	36	0.02	<10	9	<10	<1	47
72	81573	<0.2	0.32	15	45	10	0.72	2	9	128	11	3.07	<10	0.73	320	<1	0.03	22	310	20	<5	<20	44	0.01	<10	5	<10	<1	30
73	81574	<0.2	0.34	25	50	<5	0.57	2	11	92	14	2.86	<10	0.65	325	<1	0.02	21	310	18	<5	<20	30	0.01	<10	5	<10	<1	74
74	81575	<0.2	0.35	30	55	<5	1.06	1	9	184	23	2.32	10	0.54	461	<1	0.03	21	320	20	<5	<20	70	<0.01	<10	5	<10	<1	35
75	81576	0.2	0.40	20	60	<5	0.66	<1	9	140	22	2.36	<10	0.20	398	<1	0.03	14	320	12	<5	<20	38	0.01	<10	5	<10	2	20

QC DATA:**Repeat:**

1	81501	<0.2	1.42	20	40	<5	2.82	<1	15	94	23	3.37	<10	0.75	413	<1	0.01	30	750	32	<5	<20	189	0.01	<10	14	<10	<1	67
10	81511	<0.2	1.05	15	50	<5	1.28	<1	12	116	23	2.80	<10	0.73	478	<1	0.02	24	470	26	<5	<20	74	0.01	<10	10	<10	<1	48
19	81520	<0.2	0.57	20	75	<5	0.79	1	11	136	29	3.15	30	0.60	515	<1	0.03	25	570	14	<5	<20	45	0.01	<10	6	<10	<1	41
36	81537	0.6	0.33	45	65	5	3.08	1	15	146	19	3.16	<10	0.86	636	<1	0.02	30	450	26	<5	<20	213	0.02	<10	6	<10	<1	28
45	81546	0.5	0.34	45	65	10	0.94	2	11	163	15	3.07	<10	0.73	325	<1	0.02	26	270	42	<5	<20	97	0.01	<10	6	<10	<1	38
54	81555	0.4	0.46	20	75	5	0.59	2	15	108	24	3.64	<10	0.63	329	2	0.03	27	460	18	<5	<20	37	0.01	<10	6	<10	<1	42
71	81572	0.4	0.60	41	100	8	0.55	1	27	77	41	4.64	<10	0.62	410	1	0.03	41	485	31	<5	<20	40	0.02	<10	9	<10	<1	47

Resplit:

1	81501	<0.2	1.44	15	45	10	2.84	1	14	102	28	3.39	<10	0.77	412	<1	0.01	31	790	32	<5	<20	197	0.03	<10	14	<10	1	69
36	81537	0.6	0.32	50	55	5	3.13	2	14	136	18	3.12	<10	0.89	652	<1	0.02	30	460	24	<5	<20	213	0.02	<10	6	<10	<1	31
71	81572	0.5	0.66	41	98	13	0.47	2	27	83	41	4.66	<10	0.55	392	<1	0.04	44	485	32	<5	<20	32	0.03	<10	11	<10	<1	49

Standard:

Pb129a		11.7	0.84	10	80	<5	0.45	59	6	11	1423	1.58	<10	0.69	366	3	0.03	9	400	6036	15	<20	33	0.02	<10	18	<10	<1	9948
Pb129a		11.8	0.84	10	70	<5	0.45	59	6	11	1452	1.59	<10	0.70	369	2	0.03	8	400	6046	15	<20	29	0.02	<10	18	<10	<1	>10000
Pb129a		12.0	0.82	15	65	<5	0.49	59	6	12	1409	1.56	<10	0.68	363	2	0.03	8	410	6030	15	<20	31	0.02	<10	18	<10	<1	>10000

ECO TECH LABORATORY LTD.

Jutta Jealouse

B.C. Certified Assayer

JJ/ndw
df/994s
XLS/08

CERTIFICATE OF ASSAY AK 2008-1018

Manson Creek Resources

29-Aug-08

Suite 500, 926 - 5 Avenue S.W.

Calgary, AB

T2P 0N7

No. of samples received: 61

Sample Type: Core

Project: Meridian

Submitted by: Stephens Rowins

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	81577	<0.03	<0.001
2	81578	<0.03	<0.001
3	81579	<0.03	<0.001
4	81580	<0.03	<0.001
5	81581	<0.03	<0.001
6	81582	<0.03	<0.001
7	81583	<0.03	<0.001
8	81584	<0.03	<0.001
9	81585	<0.03	<0.001
10	81586	<0.03	<0.001
11	81587	<0.03	<0.001
12	81588	<0.03	<0.001
13	81589	<0.03	<0.001
14	81590	<0.03	<0.001
15	81591	<0.03	<0.001
16	81592	<0.03	<0.001
17	81593	<0.03	<0.001
18	81594	<0.03	<0.001
19	81595	<0.03	<0.001
20	81596	<0.03	<0.001
21	81597	<0.03	<0.001
22	81598	<0.03	<0.001
23	81599	<0.03	<0.001
24	81600	<0.03	<0.001
25	B324301	<0.03	<0.001
26	B324302	<0.03	<0.001
27	B324303	<0.03	<0.001
28	B324304	<0.03	<0.001
29	B324305	<0.03	<0.001
30	B324306	<0.03	<0.001
31	B324307	<0.03	<0.001
32	B324308	<0.03	<0.001

ECO TECH LABORATORY LTD.

Jutta Jealouse

B.C. Certified Assayer

ET #.	Tag #	Au (g/t)	Au (oz/t)
33	B324309	0.40	0.012
34	B324310	<0.03	<0.001
35	B324311	<0.03	<0.001
36	B324312	<0.03	<0.001
37	B324313	<0.03	<0.001
38	B324314	<0.03	<0.001
39	B324315	<0.03	<0.001
40	B324316	<0.03	<0.001
41	B324317	<0.03	<0.001
42	B324318	<0.03	<0.001
43	B324319	<0.03	<0.001
44	B324320	0.27	0.008
45	B324321	0.26	0.008
46	B324322	<0.03	<0.001
47	B324323	<0.03	<0.001
48	B324324	<0.03	<0.001
49	B324325	<0.03	<0.001
50	B324326	<0.03	<0.001
51	B324327	<0.03	<0.001
52	B324328	<0.03	<0.001
53	B324329	<0.03	<0.001
54	B324330	<0.03	<0.001
55	B324331	<0.03	<0.001
56	B324332	<0.03	<0.001
57	B324333	<0.03	<0.001
58	B324334	<0.03	<0.001
59	B324335	0.08	0.002
60	B324336	<0.03	<0.001
61	B324337	3.60	0.105

QC DATA:**Repeat:**

1	81577	<0.03	<0.001
10	81586	<0.03	<0.001
19	81595	<0.03	<0.001
33	B324309	0.37	0.011
36	B324312	<0.03	<0.001
44	B324320	0.33	0.010
45	B324321	0.24	0.007
54	B324330	<0.03	<0.001
61	B324337	3.50	0.102

Resplit:

1	81577	<0.03	<0.001
36	B324312	<0.03	<0.001

ECO TECH LABORATORY LTD.

Jutta Jealouse

B.C. Certified Assayer

Manson Creek Resources AK8-1018

29-Aug-08

ET #.	Tag #	Au (g/t)	Au (oz/t)
Standard:			
OXI67		1.82	0.053
OXI67		1.80	0.052

JJ/nw
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

#####

ECO TECH LABORATORY LTD.

10041 Dallas Drive

KAMLOOPS, B.C.

V2C 6T4

ICP CERTIFICATE OF ANALYSIS AW 2008- 1018**Manson Creek Resources**

Suite 500, 926 - 5 Avenue S.W.

Calgary, AB

T2P 0N7

Phone: 250-573-5700

Fax : 250-573-4557

*No. of samples received: 61**Sample Type: Core**Project: Meridian**Submitted by: Stephens Rowins**Values in ppm unless otherwise reported*

Et #.	Tag #	Ag ppm	Al %	As ppm	Ba ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppb	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Se ppm	Sr ppm	Te ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
1	81577	0.1	0.24	5.6	35.5	0.20	0.79	0.05	4.8	119.5	11.99	1.45	1.1	10	0.14	10.5	0.31	282	1.09	0.041	13.9	203	18.23	0.12	0.42	0.8	0.2	46.5	<0.02	10.1	0.005	0.10	0.8	2	0.1	25.6
2	81578	0.1	0.25	6.6	36.0	0.22	0.83	0.04	5.7	73.0	8.79	1.40	1.0	5	0.14	10.0	0.28	271	0.54	0.041	9.2	230	15.38	0.14	0.54	0.8	0.2	52.5	0.02	10.0	0.005	0.12	1.0	<2	<0.1	23.6
3	81579	0.1	0.35	10.5	45.5	0.34	0.21	0.47	9.0	44.5	26.49	2.40	1.5	15	0.18	22.0	0.20	278	0.51	0.033	15.5	365	14.71	0.08	0.56	1.2	0.4	19.0	0.04	13.9	0.005	0.10	1.1	2	<0.1	210.2
4	81580	0.1	0.41	5.9	39.0	0.32	0.44	0.03	7.1	88.0	10.84	2.02	1.6	10	0.16	14.5	0.41	294	0.52	0.037	14.4	281	21.93	0.14	0.52	0.9	0.2	34.0	0.02	11.7	0.005	0.08	1.1	2	<0.1	32.1
5	81581	0.1	0.34	12.6	38.5	0.26	0.82	0.02	7.7	86.0	11.70	2.28	1.2	5	0.16	13.5	0.52	408	0.45	0.034	14.7	245	13.20	0.14	0.26	0.8	0.3	51.0	0.02	11.4	0.005	0.08	1.0	2	<0.1	33.7
6	81582	0.2	0.32	42.1	52.5	0.40	0.71	0.08	9.1	82.0	26.82	2.58	1.2	<5	0.20	13.0	0.50	501	0.44	0.037	17.3	302	26.35	0.30	0.30	1.3	0.3	55.5	0.02	13.6	0.005	0.08	1.3	2	<0.1	33.2
7	81583	0.1	0.27	54.7	47.0	0.24	1.50	0.03	8.9	66.5	19.47	2.45	1.0	<5	0.18	13.0	0.69	500	0.55	0.037	19.8	312	13.93	0.28	0.24	1.3	0.2	98.5	0.04	11.8	0.005	0.08	1.0	<2	<0.1	29.5
8	81584	0.2	0.43	25.4	59.5	0.28	0.21	0.19	9.6	79.5	16.18	2.83	1.7	<5	0.20	24.0	0.21	449	0.47	0.039	19.4	352	13.76	0.06	0.28	1.5	0.3	18.0	0.02	14.5	0.005	0.08	1.0	2	<0.1	61.5
9	81585	0.2	0.36	24.8	50.0	0.32	0.37	0.03	10.0	47.0	29.47	2.76	1.7	<5	0.19	34.0	0.64	325	0.27	0.034	20.6	376	16.66	0.06	0.28	1.3	0.4	29.5	0.04	16.6	0.005	0.08	1.4	2	<0.1	58.3
10	81586	0.1	0.39	38.9	43.5	0.32	3.28	0.10	17.5	67.0	39.28	4.01	1.4	5	0.17	15.0	1.25	1061	0.95	0.048	38.9	613	18.93	0.08	0.52	3.6	0.2	172.0	0.04	9.4	0.005	0.08	0.7	6	<0.1	59.6
11	81587	0.1	0.40	10.8	54.0	0.34	0.83	0.04	8.1	64.0	21.65	2.82	1.8	10	0.20	31.5	0.71	442	0.30	0.043	18.5	341	28.23	0.06	0.20	1.6	0.3	51.0	0.02	15.3	0.005	0.08	1.2	<2	<0.1	50.4
12	81588	0.1	0.23	12.1	34.0	0.18	2.53	0.06	7.5	87.0	21.09	1.82	1.0	<5	0.12	12.5	0.52	645	0.73	0.045	14.1	335	16.89	0.06	0.18	1.5	0.2	134.0	0.02	10.7	0.005	0.06	0.7	4	<0.1	23.2
13	81589	<0.1	0.62	14.6	45.0	0.22	2.72	0.07	12.3	57.5	21.88	3.38	2.2	<5	0.17	15.5	0.92	884	0.59	0.048	25.9	480	12.78	0.08	0.18	2.4	0.2	142.5	0.02	10.5	0.005	0.06	0.7	8	<0.1	52.2
14	81590	0.1	0.95	18.7	50.0	0.24	2.97	0.12	16.1	60.5	31.02	4.76	3.8	5	0.18	12.5	1.26	1064	0.93	0.042	28.9	1300	12.14	0.14	0.26	4.1	0.2	169.5	<0.02	10.6	0.001	0.06	0.9	12	<0.1	69.7
15	81591	0.1	1.38	9.2	60.5	0.38	0.98	0.08	10.4	77.0	26.94	3.16	4.5	<5	0.23	13.0	0.90	360	0.96	0.037	24.6	463	16.87	0.20	0.34	1.6	0.4	70.0	0.04	15.4	0.001	0.08	1.7	10	<0.1	73.3
16	81592	0.1	0.60	20.8	38.5	0.54	4.62	0.25	11.5	50.5	33.33	3.60	2.3	10	0.19	3.0	0.91	828	2.11	0.035	31.2	842	24.75	1.44	1.90	3.0	1.1	241.5	0.12	6.7	0.001	0.08	0.5	8	<0.1	74.8
17	81593	0.1	0.85	12.3	39.0	0.40	3.27	0.21	13.0	49.5	32.42	4.05	2.9	5	0.17	4.0	1.05	979	1.98	0.036	29.8	1044	13.58	1.32	1.36	2.4	0.6	160.5	0.06	6.1	0.001	0.06	0.5	10	<0.1	57.2
18	81594	0.1	4.44	5.8	10.5	<0.02	6.08	0.10	30.6	19.0	22.03	10.96	21.8	<5	0.03	13.0	2.84	2090	2.17	0.042	6.3	7883	5.11	0.52	0.34	18.5	0.5	289.5	<0.02	0.9	0.008	0.02	0.1	156	<0.1	130.9
19	81595	0.1	2.48	39.7	42.0	0.22	5.21	0.13	32.3	450.5	26.64	6.39	8.8	5	0.14	3.5	3.02	1049	2.46	0.034	224.4	1059	16.23	0.92	0.88	7.2	0.6	243.5	0.06	5.2	0.001	0.06	0.5	50	<0.1	125.6
20	81596	0.1	0.88	9.8	36.0	0.18	3.45	0.14	12.5	48.0	22.73	3.71	3.3	10	0.16	3.5	0.92	579	0.92	0.039	21.8	1564	12.62	1.28	1.64	2.9	0.6	156.5	0.04	4.9	0.001	0.06	0.4	18	<0.1	66.1
21	81597	0.1	0.89	11.3	36.0	0.22	2.84	0.09	11.4	60.5	19.38	3.22	3.0	10	0.16	4.0	0.75	486	0.82	0.035	24.1	903	19.50	1.16	2.68	2.3	0.5	127.5	0.06	5.4	0.001	0.04	0.5	12	<0.1	54.0
22	81598	0.1	0.37	9.8	36.5	0.16	3.86	0.08	8.5	65.0	18.32	2.45	1.3	5	0.13	3.5	0.63	691	0.67	0.038	19.3	412	15.74	0.86	1.46	1.5	0.4	192.0	0.02	5.2	0.005	0.04	0.4	4	<0.1	30.5
23	81599	0.1	1.16	6.1	38.0	0.44	0.53	0.08	9.6	57.5	25.46	2.69	3.7	5	0.16	13.5	0.63	278	0.44	0.033	22.0	317	23.18	0.30	1.04	1.1	0.3	33.0	0.04	13.7	0.005	0.06	1.9	8	<0.1	61.3
24	81600	0.1	1.16	7.2	36.5	0.34	0.35	0.12	11.3	70.5	21.66	2.72	3.8	10	0.15	13.5	0.56	207	0.67	0.031	23.5	349	19.93	0.30	1.00	1.0	0.2	22.5	0.02	14.9	0.001	0.06	1.0	8	<0.1	71.0
25	B324301	0.1	0.81	6.5	29.0	0.24	0.53	0.10	7.3	71.0	14.66	2.37	2.6	5	0.12	9.5	0.47	242	0.87	0.032	16.8	247	22.64	0.30	1.00	0.9	0.2	27.5	0.02	9.6	0.005	0.04	0.8	6	<0.1	51.5
26	B324302	0.1	1.05	5.3	30.0	0.32	0.36	0.13	8.6	60.5	20.57	2.60	3.5	5	0.13	11.5	0.56	215	0.53	0.036	19.8	283	19.28	0.22	0.90	1.1	0.2	20.5	0.04	11.6	0.005	0.04	1.0	6	<0.1	63.0
27	B324303	0.1	0.48	5.4	21.0	0.18	0.28	0.01	3.8	106.0	7.60	1.38	1.6	5	0.09	7.5	0.25	136	0.94	0.036	10.4	177	22.98	0.12	0.76	0.7	0.2	16.5	<0.02	4.9	0.005	0.04	0.4	4	<0.1	26.5
28	B324304	0.2	0.65	4.7	35.5	0.26	0.35	0.16	5.9	89.0	16.24	1.78	2.4	10	0.13	18.5	0.30	202	0.58	0.028	14.5	229	21.73	0.08	0.64	0.8	0.2	18.5	0.02	11.9	0.005	0.06	0.9	4	<0.1	53.6
29	B324305	0.4	0.33	14.0	35.0	0.36	0.24	0.28	7.7	64.0	17.15	2.47	1.1	15	0.13	9.5	0.16	236	1.27	0.027	16.9	248	22.44	0.42	1.46	0.9	0.4	14.5	0.04	10.3	0.005	0.06	0.9	2	<0.1	56.7
30	B324306	0.3	0.45	8.9	36.0	0.38	0.37	0.08	8.6	64.5	21.09	2.65	1.7	10	0.15	20.0	0.50	256	0.64	0.027	18.3	357	11.01	0.16	1.04	1.2	0.3	23.0	0.04	14.4	0.005	0.06	1.4	2	<0.1	50.8

Et #.	Tag #	Ag ppm	Al %	As ppm	Ba ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppb	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Se ppm	Sr ppm	Te ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
31	B324307	0.3	0.12	25.4	17.0	0.08	0.04	0.12	4.0	108.5	4.77	1.45	0.4	<5	0.07	5.0	0.07	144	0.42	0.026	9.6	112	42.71	0.42	0.56	0.8	0.2	3.5	<0.02	4.5	0.005	0.04	0.4	<2	<0.1	14.2
32	B324308	0.1	0.02	14.0	1.5	<0.02	0.56	0.02	1.8	136.5	4.14	0.68	0.1	<5	<0.01	0.5	0.17	122	0.49	0.021	7.2	5	7.43	0.18	0.20	0.8	<0.1	38.0	<0.02	0.3	0.005	<0.02	<0.1	<2	<0.1	2.6
33	B324309	1.7	0.11	974.0	5.0	0.14	1.92	0.18	21.8	113.0	12.41	11.77	0.5	5	0.05	0.5	1.33	906	0.34	0.033	46.3	296	106.50	9.18	3.46	3.1	0.2	165.5	0.02	0.5	0.005	0.02	<0.1	2	<0.1	30.6
34	B324310	0.1	0.16	10.5	24.0	0.14	0.49	0.02	4.1	98.0	5.98	1.46	0.7	5	0.10	11.0	0.31	220	0.68	0.037	9.3	194	6.37	0.12	0.62	0.8	0.2	26.5	<0.02	9.1	0.005	0.04	0.7	<2	<0.1	11.4
35	B324311	0.1	0.29	10.3	29.5	0.22	0.67	0.05	5.7	83.5	14.88	2.01	1.2	15	0.12	12.5	0.45	315	0.45	0.030	12.9	228	19.88	0.14	0.60	1.0	0.2	33.0	<0.02	10.5	0.005	0.04	0.7	<2	<0.1	39.8
36	B324312	0.2	0.28	11.7	33.5	0.38	1.41	0.04	10.1	107.0	6.09	1.84	1.1	5	0.15	9.5	0.41	451	1.01	0.033	17.6	321	14.86	0.42	1.20	1.1	0.3	70.0	<0.02	9.0	0.005	0.06	1.0	2	<0.1	16.8
37	B324313	0.2	0.78	9.1	34.0	0.34	0.56	0.02	12.3	95.0	24.98	2.61	2.6	10	0.14	11.5	0.54	319	0.99	0.038	23.7	343	15.03	0.38	1.10	1.3	0.2	34.0	<0.02	9.3	0.005	0.06	0.9	6	<0.1	43.9
38	B324314	0.1	0.58	4.4	23.5	0.26	1.02	0.02	5.8	96.0	19.01	2.27	2.2	5	0.10	11.0	0.55	462	0.47	0.046	14.9	218	21.74	0.16	0.38	1.3	0.2	62.0	<0.02	8.8	0.005	0.04	0.8	4	<0.1	34.6
39	B324315	0.1	0.67	7.1	34.5	0.38	0.54	0.01	9.8	101.0	14.18	2.01	2.4	10	0.14	11.5	0.41	245	0.64	0.042	17.8	275	11.88	0.26	0.78	0.9	0.2	31.0	0.04	9.2	0.005	0.06	1.1	6	<0.1	31.2
40	B324316	0.2	0.84	6.3	26.5	0.22	1.90	0.03	7.1	81.0	52.74	3.53	4.0	5	0.10	11.5	0.80	742	1.26	0.044	13.0	1062	10.62	0.14	0.34	3.9	0.3	116.5	0.04	7.7	0.001	0.04	0.8	6	<0.1	58.4
41	B324317	0.2	1.21	7.0	41.5	0.52	0.51	<0.01	10.4	82.5	19.93	3.05	4.2	5	0.16	28.0	0.70	365	0.63	0.033	25.6	372	16.57	0.06	0.16	1.1	0.4	45.5	0.04	15.1	0.001	0.06	1.3	8	<0.1	54.0
42	B324318	0.2	0.85	5.5	34.0	0.30	0.52	0.03	6.9	63.0	15.48	2.41	3.4	<5	0.11	21.0	0.53	367	0.34	0.038	15.7	294	15.98	0.04	0.18	1.0	0.3	36.5	<0.02	13.0	0.001	0.04	1.0	6	<0.1	45.6
43	B324319	0.5	0.23	13.6	49.5	1.62	1.39	0.05	6.9	80.0	31.52	2.71	1.1	<5	0.15	17.5	0.70	829	0.39	0.040	12.5	245	76.97	0.08	0.16	1.8	0.4	144.5	0.04	11.3	0.005	0.06	0.9	<2	<0.1	31.4
44	B324320	1.1	0.21	47.5	20.5	0.62	2.55	0.13	14.2	67.0	22.53	3.51	0.7	15	0.15	2.5	0.72	531	2.13	0.041	36.8	226	27.53	2.46	4.78	2.0	0.9	153.5	0.18	7.3	0.005	0.06	0.9	2	<0.1	30.4
45	B324321	1.1	0.22	51.5	22.5	0.62	2.42	0.08	12.6	64.0	26.50	3.25	0.7	15	0.16	4.0	0.70	510	1.66	0.037	35.6	413	21.85	2.10	4.84	1.8	0.8	158.0	0.16	7.2	0.005	0.06	0.8	<2	<0.1	35.4
46	B324322	1.4	0.21	41.7	49.5	0.42	0.53	0.04	8.8	68.5	23.39	2.61	0.9	5	0.18	16.5	0.55	298	0.81	0.042	21.5	342	13.18	0.24	0.86	1.1	0.3	35.5	0.04	13.1	0.005	0.06	2.4	<2	<0.1	41.7
47	B324323	0.6	0.22	28.3	27.0	0.34	3.52	0.30	12.9	65.0	46.53	3.64	0.7	15	0.15	2.5	0.87	561	1.42	0.034	33.7	487	30.10	1.96	2.38	2.7	0.9	196.0	0.04	6.8	0.005	0.04	0.7	2	<0.1	73.5
48	B324324	0.3	0.17	17.1	30.0	0.12	3.63	0.15	8.6	94.0	26.63	3.16	0.6	5	0.12	2.0	0.84	606	1.07	0.030	25.6	421	25.84	1.22	0.84	2.8	0.6	229.0	0.04	5.1	0.005	0.02	0.5	2	<0.1	45.3
49	B324325	0.3	0.19	13.0	32.5	0.14	3.42	0.09	7.9	95.0	10.41	2.66	0.7	10	0.12	3.0	0.81	601	0.79	0.041	20.3	377	15.01	0.76	1.14	2.7	0.4	232.5	0.04	5.0	0.005	0.04	0.4	2	<0.1	22.8
50	B324326	0.4	0.20	17.8	37.5	0.16	2.09	0.12	8.9	81.5	19.02	2.24	0.7	10	0.13	4.5	0.53	397	0.71	0.032	22.4	353	13.47	1.06	2.00	1.7	0.5	131.0	0.02	5.8	0.005	0.06	0.5	<2	<0.1	38.7
51	B324327	0.6	0.23	18.9	30.0	0.54	1.66	0.14	11.5	64.5	26.84	3.16	0.8	15	0.15	5.5	0.65	289	1.17	0.035	27.9	455	12.91	1.46	2.92	2.4	0.7	109.5	0.04	6.4	0.005	0.06	0.6	2	<0.1	52.9
52	B324328	0.2	0.19	19.6	35.0	0.20	4.31	0.14	10.5	79.5	16.35	3.07	0.6	15	0.13	2.5	0.81	691	1.06	0.039	26.0	413	24.40	1.32	1.00	2.4	0.7	246.5	0.04	5.8	0.005	0.04	0.7	2	<0.1	53.0
53	B324329	0.4	0.20	24.0	36.5	0.20	2.88	0.07	11.0	70.0	13.37	2.25	0.7	15	0.13	4.0	0.63	647	0.62	0.035	23.5	366	41.69	0.80	2.20	1.8	0.3	130.0	0.04	5.4	0.005	0.04	0.7	<2	<0.1	17.2
54	B324330	0.3	0.18	19.2	31.5	0.20	4.24	0.39	9.0	94.5	7.94	2.44	0.7	20	0.12	4.0	0.78	883	0.64	0.047	19.5	462	81.20	0.62	1.54	2.3	0.3	206.0	0.04	4.5	0.005	0.04	0.5	<2	<0.1	81.0
55	B324331	0.3	0.27	41.7	38.5	0.52	0.73	0.11	12.5	63.0	26.89	3.96	1.2	10	0.17	25.0	0.90	654	0.37	0.041	26.9	370	41.17	0.06	0.42	1.8	0.3	44.5	0.04	15.9	0.005	0.06	1.9	<2	<0.1	80.3
56	B324332	0.3	0.19	40.8	40.5	0.40	1.03	0.14	8.8	95.5	25.19	2.45	0.8	5	0.13	14.0	0.60	676	0.39	0.040	24.1	272	47.88	0.06	0.42	1.5	0.2	57.0	<0.02	10.7	0.005	0.04	1.0	<2	<0.1	61.6
57	B324333	0.3	0.30	35.1	36.0	0.46	0.58	0.06	11.6	76.5	28.10	3.53	1.3	10	0.15	23.0	0.85	633	0.50	0.049	28.6	360	33.01	0.04	0.40	1.8	0.2	34.0	0.04	13.8	0.005	0.04	1.4	<2	<0.1	67.2
58	B324334	0.2	0.34	28.4	38.0	0.40	0.40	0.03	11.8	70.5	27.84	3.39	1.5	5	0.16	24.0	0.80	513	0.47	0.048	30.1	389	20.17	0.08	0.38	1.7	0.2	26.0	0.04	15.3	0.005	0.06	1.5	2	<0.1	56.8
59	B324335	0.9	0.25	78.5	29.5	0.54	1.45	0.36	16.9	72.5	43.54	3.53	0.8	15	0.15	6.0	0.82	452	2.28	0.041	38.8	301	62.04	1.48	3.48	1.8	0.3	84.5	0.04	11.3	0.005	0.06	1.1	2	<0.1	77.3
60	B324336	0.4	0.24	33.2	39.0	0.32	2.17	0.06	11.4	79.0	19.56	3.96	0.8	10	0.15	8.0	1.06	706	0.65	0.044	29.6	362	15.06	0.64	2.00	2.2	0.3	104.5	0.04	9.6	0.005	0.04	0.7	<2	<0.1	35.7
61	B324337	1.4	0.17	98.4	31.0	0.28	2.70	0.09	10.6	86.0	11.22	2.91	0.6	10	0.12	4.0	0.71	477	0.57	0.048	28.7	75	18.27	1.24	1.28	2.1	0.5	172.5	0.04	6.2	0.005	0.04	0.8	<2	<0.1	32.3
QC DATA:																																				
Repeat:																																				
1	81577	0.1	0.26	5.7	34.5	0.18	0.81	0.05	4.9	114.5	11.86	1.46	1.0	5	0.14	9.5	0.31	287	0.90	0.042	13.9	206	17.82	0.12	0.42	0.8	0.1	49.0	<0.02	10.5	0.005	0.08	0.8	2	<0.1	26.0
10	81586	0.1	0.36	40.1	43.5	0.32	3.22	0.09	17.0	63.5	38.35	3.91	1.3	5	0.16	14.0	1.20	1048	0.89	0.045	37.9	586	20.42	0.08	0.52	3.5	0.2	174.5	0.02	9.2	0.005	0.06	0.7	6	<0.1	58.3
19	81595	0.1	2.42	40.4	40.5	0.22	5.01	0.14	31.4	442.5	26.91	6.33	8.6	5	0.14	3.5	2.99	1040	2.33	0.027	221.5	1030	17.52	0.90	0.92	7.1	0.6	239.0	0.04	5.3	0.001	0.04	0.5	48	<0.1	123.1
36	B324312	0.1	0.29	11.4	32.5	0.36	1.36	0.04	9.8	102.5	6.03	1.79	1.0	10	0.14	9.5	0.40	437	1.02	0.034	17.0	312	13.76	0.42	1.18	1.0	0.3	68.0	0.02	8.9	0.005	0.06	0.9	<2	<0.1	15.6
45	B324321	1.0	0.20	50.8	22.5	0.58	2.39	0.07	12.3	61.5	25.66	3.19	0.6	10	0.15	3.5	0.68	499	1.79	0.036	33.9	388	20.35	2.06	5.04	1.8	0.7	156.0	0.14	7.2	0.005	0				

Et #.	Tag #	Ag ppm	Al %	As ppm	Ba ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppb	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Se ppm	Sr ppm	Te ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm				
Standard:																																								
Pb129a		11.4	0.86	6.2	60.0	0.40	0.54	56.63	4.8	11.5	1435.00	1.57	2.4	80	0.11	4.0	0.68	381	2.06	0.045	5.2	436	6256.00	0.80	16.46	0.8	0.2	29.5	0.14	0.5	0.035	0.04	0.1	16	<0.1	>10000				
Pb129a		12.1	0.79	5.7	60.0	0.38	0.57	64.34	4.7	11.5	1407.00	1.63	2.5	75	0.11	4.0	0.73	403	2.36	0.059	5.2	476	6152.00	0.72	18.40	0.8	0.2	31.0	0.16	0.5	0.035	0.04	0.1	17	<0.1	>10000				

ECO TECH LABORATORY LTD.

Jutta Jealous
B.C. Certified Assayer

JJ/sa
df/msr1018
XLS/07

CERTIFICATE OF ASSAY AK 2008- 1059

Manson Creek Resources

23-Sep-08

Suite 500, 926 - 5 Avenue S.W.

Calgary, AB

T2P 0N7

No. of samples received: 99

Sample Type: Core + Rock

Project: Meridian

Submitted by: Regan Chernish

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	B324338	0.03	0.001		
2	B324339	0.03	0.001		
3	B324340	<0.03	<0.001		
4	B324341	<0.03	<0.001		
5	B324342	<0.03	<0.001		
6	B324343	0.04	0.001		
7	B324344	<0.03	<0.001		
8	B324345	<0.03	<0.001		
9	B324346	<0.03	<0.001		
10	B324347	<0.03	<0.001		
11	B324348	<0.03	<0.001		
12	B324349	<0.03	<0.001		
13	B324350	0.06	0.002		
14	B324351	<0.03	<0.001		
15	B324352	<0.03	<0.001		
16	B324353	<0.03	<0.001		
17	B324354	0.03	0.001		
18	B324355	<0.03	<0.001		
19	B324356	<0.03	<0.001		
20	B324357	<0.03	<0.001		
21	B324358	<0.03	<0.001		
22	B324359	<0.03	<0.001		
23	B324360	<0.03	<0.001		
24	B324361	<0.03	<0.001		
25	B324362	<0.03	<0.001		
26	B324363	<0.03	<0.001		
27	B324364	<0.03	<0.001		
28	B324365	<0.03	<0.001		
29	B324366	<0.03	<0.001		

ECO TECH LABORATORY LTD.

Jutta Jealouse

B.C. Certified Assayer

Manson Creek Resources AK8-1059

23-Sep-08

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
30	B324367	<0.03	<0.001		
31	B324368	2.16	0.063		
32	B324369	1.00	0.029		
33	B324370	0.67	0.020		
34	B324371	0.03	0.001		
35	B324372	0.20	0.006		
36	B324373	0.03	0.001		
37	B324374	0.04	0.001		
38	B324375	0.03	0.001		
39	B324376	0.04	0.001		
40	B324377	<0.03	<0.001		
41	B324378	0.06	0.002		
42	B324379	<0.03	<0.001		
43	B324380	<0.03	<0.001		
44	B324381	<0.03	<0.001		
45	B324382	<0.03	<0.001		
46	B324383	<0.03	<0.001		
47	B324384	0.51	0.015		
48	B324385	0.08	0.002		
49	B324386	0.19	0.006		
50	B324387	0.04	0.001		
51	B324388	0.06	0.002		
52	B324389	0.07	0.002		
53	B324390	0.04	0.001		
54	B324391	0.04	0.001		
55	B324392	<0.03	<0.001		
56	B324393	<0.03	<0.001		
57	B324394	0.06	0.002		
58	B324395	<0.03	<0.001		
59	B324396	<0.03	<0.001		
60	B324397	<0.03	<0.001		
61	B324398	<0.03	<0.001		
62	B323720	<0.03	<0.001		
63	B323721	0.05	0.001		
64	B323722	0.03	0.001		
65	B323723	<0.03	<0.001		
66	B323724	<0.03	<0.001		
67	B323725	<0.03	<0.001		
68	B323726	<0.03	<0.001		

ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

Manson Creek Resources AK8-1059

23-Sep-08

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
69	B323727	0.03	0.001		
70	B323728	<0.03	<0.001		
71	B323729	0.55	0.016		
72	B323730	<0.03	<0.001		
73	B323731	<0.03	<0.001		
74	B323732	<0.03	<0.001		
75	B323733	0.37	0.011		
76	B323734	<0.03	<0.001		
77	B323735	<0.03	<0.001		
78	B323736	<0.03	<0.001		
79	B323737	<0.03	<0.001		
80	B323738	0.05	0.001		
81	B323739	2.06	0.060		
82	B323740	1.98	0.058		
83	B323741	1.19	0.035		
84	B323742	0.04	0.001		
85	B323743	<0.03	<0.001		
86	B323744	<0.03	<0.001		
87	B323745	<0.03	<0.001		
88	B323746	<0.03	<0.001		
89	B323747	<0.03	<0.001		
90	B323748	<0.03	<0.001		
91	B323749	<0.03	<0.001		
92	B323750	<0.03	<0.001		
93	B323717	194	5.658		
94	B323718	1.54	0.045		
95	B323719	0.82	0.024		
96	B315219	0.12	0.003		
97	B315220	0.05	0.001		
98	B315221	0.61	0.018		
99	B315222	0.06	0.002		

QC DATA:

Repeat:

1	B324338	<0.03	<0.001		
10	B324347	<0.03	<0.001		
19	B324356	<0.03	<0.001		
31	B324368	2.04	0.059		
32	B324369	0.94	0.027		
36	B324373	<0.03	<0.001		
45	B324382	<0.03	<0.001		
54	B324391	<0.03	<0.001		

ECO TECH LABORATORY LTD.

Jutta Jealous

B.C. Certified Assayer

Manson Creek Resources AK8-1059

23-Sep-08

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
71	B323729	0.55	0.016		
80	B323738	0.07	0.002		
81	B323739	2.24	0.065		
82	B323740	2.11	0.062		
83	B323741	1.08	0.031		
89	B323747	<0.03	<0.001		
93	B323717	1.94	0.057	48.1	1.40
95	B323719	0.79	0.023		
98	B315221	0.57	0.017		
Resplit:					
1	B324338	<0.03	<0.001		
36	B324373	0.03	0.001		
71	B323729	0.63	0.018		
Standard:					
	Ox167	1.78	0.052		
	Ox167	1.78	0.052		
	Ox167	1.82	0.053		
	Pb129			24.2	0.71

JJ/nw
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

ECO TECH LABORATORY LTD.

10041 Dallas Drive

KAMLOOPS, B.C.

V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 2008- 1059**Manson Creek Resources**

Suite 500, 926 - 5 Avenue S.W.

Calgary, AB

T2P 0N7

Phone: 250-573-5700

Fax : 250-573-4557

*No. of samples received: 99**Sample Type: Core +Rock****Project: Meridian****Submitted by: Regan Chernish**Values in ppm unless otherwise reported*

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	B324338	<0.2	0.29	5	35	<5	0.75	<1	11	141	16	2.15	<10	0.21	296	2	0.03	15	1060	8	<5	<20	44	0.03	<10	7	<10	2	17
2	B324339	0.2	0.41	30	50	<5	0.34	<1	17	152	13	2.34	10	<0.01	591	4	0.03	23	1430	14	<5	<20	25	0.03	<10	7	<10	3	46
3	B324340	0.2	0.18	<5	25	<5	0.90	<1	7	140	15	1.59	<10	0.17	458	<1	0.03	8	250	6	<5	<20	40	0.03	<10	5	<10	1	12
4	B324341	<0.2	0.24	10	25	<5	1.67	<1	9	166	11	2.39	<10	0.45	578	2	0.03	13	750	6	5	<20	94	0.03	<10	5	<10	2	18
5	B324342	<0.2	0.18	10	20	<5	1.52	<1	10	115	17	1.97	<10	0.39	486	<1	0.02	9	390	8	<5	<20	86	0.04	<10	4	<10	1	14
6	B324343	0.2	0.36	30	45	<5	0.53	2	23	80	29	3.27	<10	0.46	285	6	0.02	31	380	14	20	<20	27	0.03	<10	5	<10	<1	33
7	B324344	<0.2	0.19	<5	20	<5	0.64	<1	7	129	9	1.50	<10	0.25	235	<1	0.02	8	200	4	<5	<20	27	0.03	<10	3	<10	1	12
8	B324345	<0.2	0.96	<5	40	<5	0.48	1	13	70	20	2.76	10	0.75	351	4	0.02	21	400	28	20	<20	24	0.03	<10	9	<10	<1	55
9	B324346	0.2	0.30	<5	35	<5	0.44	<1	9	100	18	1.90	<10	0.31	244	2	0.02	12	280	8	<5	<20	17	0.03	<10	4	<10	<1	23
10	B324347	<0.2	0.36	<5	40	<5	1.15	<1	11	119	11	1.81	<10	0.42	350	2	0.02	13	310	12	10	<20	53	0.03	<10	5	<10	<1	18
11	B324348	<0.2	0.34	<5	40	<5	1.42	<1	7	149	18	1.68	20	0.39	447	<1	0.02	9	300	16	<5	<20	81	0.03	<10	4	<10	1	24
12	B324349	0.2	0.93	<5	55	<5	0.51	2	12	54	28	2.97	20	0.74	423	5	0.02	23	400	42	20	<20	26	0.03	<10	8	<10	<1	91
13	B324350	<0.2	0.30	<5	35	<5	0.43	<1	9	99	18	1.87	<10	0.30	241	<1	0.02	10	270	8	<5	<20	18	0.03	<10	4	<10	<1	24
14	B324351	<0.2	1.14	<5	40	<5	1.29	1	13	66	29	2.94	<10	0.74	495	3	0.01	23	370	44	<5	<20	65	0.05	<10	10	<10	<1	238
15	B324352	<0.2	0.79	<5	35	<5	4.07	1	18	73	29	3.95	<10	1.13	802	4	0.02	27	1280	20	15	<20	205	0.05	<10	14	<10	1	52
16	B324353	<0.2	0.73	<5	30	<5	3.03	2	15	55	22	3.15	<10	0.93	522	3	0.01	25	990	20	20	<20	164	0.04	<10	11	<10	1	48
17	B324354	<0.2	0.61	<5	35	<5	0.98	<1	10	101	9	2.17	<10	0.56	461	2	0.01	16	300	16	<5	<20	64	0.04	<10	6	<10	<1	33
18	B324355	<0.2	0.23	<5	25	<5	1.41	1	10	109	14	2.69	<10	0.74	484	2	0.02	18	270	38	15	<20	74	0.03	<10	4	<10	<1	30
19	B324356	0.9	0.26	<5	80	<5	0.86	<1	10	149	21	2.89	<10	0.69	374	3	0.02	20	290	14	10	<20	46	0.04	<10	4	<10	<1	41
20	B324357	<0.2	0.25	10	30	<5	0.57	<1	11	125	22	2.88	<10	0.65	302	2	0.02	19	280	12	5	<20	26	0.04	<10	4	<10	<1	47
21	B324358	<0.2	0.20	15	30	<5	0.85	<1	13	118	7	2.54	<10	0.58	328	1	0.02	20	280	22	<5	<20	45	0.04	<10	3	<10	<1	39
22	B324359	<0.2	0.27	20	35	<5	0.94	2	18	89	20	3.35	<10	0.79	357	5	0.02	28	350	22	20	<20	44	0.04	<10	4	<10	<1	54
23	B324360	<0.2	0.23	<5	25	<5	0.93	<1	10	141	12	2.74	<10	0.63	396	<1	0.02	16	260	16	<5	<20	39	0.04	<10	4	<10	<1	43
24	B324361	<0.2	0.31	<5	35	<5	0.36	1	16	49	22	3.64	<10	0.79	277	3	0.02	26	370	14	10	<20	11	0.05	<10	4	<10	<1	62
25	B324362	<0.2	0.33	<5	35	<5	0.32	2	16	72	32	3.61	10	0.86	292	3	0.02	23	380	18	15	<20	8	0.04	<10	4	<10	<1	63
26	B324363	0.2	0.23	<5	25	<5	0.82	1	13	88	23	2.92	<10	0.73	321	2	0.02	20	330	18	5	<20	35	0.04	<10	3	<10	<1	55
27	B324364	0.2	0.25	<5	25	<5	0.74	<1	12	81	22	2.88	<10	0.73	336	2	0.02	20	280	20	5	<20	28	0.04	<10	4	<10	<1	59
28	B324365	<0.2	0.19	<5	15	<5	0.45	<1	5	116	7	1.18	<10	0.18	181	<1	0.02	4	200	8	<5	<20	12	0.03	<10	3	<10	<1	22
29	B324366	<0.2	0.31	15	40	<5	0.26	1	20	72	31	3.78	<10	0.81	225	3	0.02	30	400	14	10	<20	8	0.04	<10	5	<10	<1	60
30	B324367	0.3	0.29	5	40	<5	0.41	<1	16	80	32	3.57	<10	0.87	266	1	0.02	23	330	24	<5	<20	17	0.05	<10	4	<10	<1	91

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
31	B324368	1.3	0.31	125	35	10	2.19	<1	27	84	28	5.03	<10	0.96	461	5	0.02	46	230	38	20	<20	135	0.06	<10	6	<10	<1	41
32	B324369	0.7	0.29	40	45	5	0.80	1	21	71	34	4.09	<10	0.81	345	4	0.02	34	360	24	15	<20	47	0.04	<10	4	<10	<1	77
33	B324370	0.5	0.26	<5	35	<5	1.15	<1	10	118	23	2.76	<10	0.73	349	2	0.02	18	240	38	10	<20	59	0.04	<10	4	<10	1	56
34	B324371	0.3	0.31	<5	35	5	0.38	2	15	79	30	3.86	<10	0.85	304	5	0.02	26	360	22	20	<20	15	0.04	<10	4	<10	<1	70
35	B324372	<0.2	0.23	<5	30	<5	0.58	1	11	103	16	2.48	<10	0.55	236	2	0.02	17	250	10	15	<20	28	0.03	<10	3	<10	<1	62
36	B324373	<0.2	0.17	<5	20	<5	0.89	<1	7	121	12	2.24	<10	0.43	358	<1	0.02	13	190	14	<5	<20	37	0.03	<10	3	<10	<1	31
37	B324374	<0.2	0.84	<5	35	<5	0.32	1	13	81	17	3.23	20	0.76	328	2	0.02	22	360	20	10	<20	5	0.04	<10	8	<10	<1	56
38	B324375	0.7	0.61	<5	40	<5	0.25	<1	13	112	34	3.08	20	0.69	338	4	0.02	21	360	60	10	<20	7	0.04	<10	6	<10	<1	67
39	B324376	0.3	0.22	<5	30	<5	1.59	2	10	89	18	2.97	<10	0.87	564	2	0.02	15	270	26	15	<20	92	0.04	<10	3	<10	2	69
40	B324377	<0.2	0.28	5	35	<5	0.54	<1	10	92	16	2.18	20	0.52	343	1	0.02	15	320	16	<5	<20	14	0.03	<10	3	<10	<1	36
41	B324378	0.2	0.29	10	35	<5	0.54	<1	13	103	31	2.44	10	0.57	320	<1	0.02	17	430	20	<5	<20	21	0.04	<10	4	<10	<1	59
42	B324379	0.2	0.22	10	35	5	1.03	2	15	80	19	3.54	<10	0.95	448	4	0.01	22	270	18	15	<20	52	0.04	<10	4	<10	<1	48
43	B324380	0.2	0.22	20	30	<5	0.64	1	12	82	16	2.38	10	0.71	497	3	0.02	21	340	14	15	<20	27	0.03	<10	4	<10	1	22
44	B324381	0.4	0.26	40	40	<5	0.17	<1	15	61	55	2.57	10	0.57	338	2	0.01	26	420	8	10	<20	8	0.03	<10	3	<10	<1	17
45	B324382	0.3	0.25	40	45	<5	0.98	<1	12	84	29	1.90	<10	0.60	348	<1	0.02	18	340	10	<5	<20	64	0.04	<10	3	<10	2	13
46	B324383	0.2	0.31	80	35	<5	2.79	<1	21	52	47	3.41	<10	1.43	608	<1	0.02	19	1080	12	<5	<20	158	0.10	<10	6	<10	2	22
47	B324384	2.8	0.13	1230	35	30	0.68	<1	77	73	50	>10	<10	0.14	162	12	<0.01	86	210	264	35	<20	48	0.10	<10	2	<10	<1	93
48	B324385	1.1	0.32	75	35	5	1.61	<1	27	101	28	4.51	<10	0.57	397	<1	0.01	44	750	84	<5	<20	89	0.09	<10	6	<10	<1	108
49	B324386	1.2	0.19	690	35	10	0.76	<1	37	92	41	>10	<10	0.16	126	11	<0.01	55	360	100	25	<20	45	0.07	<10	3	<10	<1	52
50	B324387	<0.2	0.21	195	30	<5	0.79	<1	20	103	8	3.35	<10	0.20	160	<1	0.01	22	280	24	<5	<20	44	0.06	<10	2	<10	<1	5
51	B324388	0.6	0.27	360	40	10	2.09	<1	55	43	10	7.10	<10	0.64	387	5	0.02	54	690	38	<5	<20	125	0.09	<10	4	<10	<1	12
52	B324389	0.4	0.27	795	35	10	0.40	<1	49	40	21	8.65	<10	0.02	47	8	0.01	81	630	34	15	<20	31	0.07	<10	3	<10	<1	25
53	B324390	0.6	0.27	365	35	<5	0.47	<1	24	21	14	3.89	<10	0.07	56	4	0.01	38	800	50	5	<20	34	0.04	<10	3	<10	<1	12
54	B324391	0.5	0.28	225	40	<5	0.80	<1	25	27	18	2.90	<10	0.18	117	1	0.01	37	900	58	<5	<20	52	0.04	<10	3	<10	2	7
55	B324392	0.2	0.28	210	35	<5	2.38	<1	26	29	9	3.39	<10	0.74	407	4	0.02	39	1040	34	20	<20	143	0.03	<10	4	<10	4	12
56	B324393	<0.2	0.32	5	45	<5	2.40	<1	4	16	1	1.44	<10	0.79	480	<1	0.01	2	810	6	<5	<20	134	0.05	<10	4	<10	5	8
57	B324394	0.5	0.24	90	30	5	1.80	3	46	48	34	6.11	<10	0.54	441	11	<0.01	80	470	16	30	<20	116	0.05	<10	5	<10	<1	31
58	B324395	<0.2	0.22	<5	35	<5	1.49	<1	7	120	9	1.93	<10	0.60	501	2	0.02	12	300	8	5	<20	68	0.03	<10	3	<10	1	12
59	B324396	<0.2	0.18	5	30	<5	0.98	<1	9	99	10	2.20	<10	0.58	405	<1	0.02	13	300	12	<5	<20	43	0.04	<10	3	<10	<1	20
60	B324397	<0.2	0.28	5	40	<5	0.66	<1	16	74	30	3.11	20	0.82	391	3	0.01	23	430	14	10	<20	18	0.04	<10	4	<10	<1	36
61	B324398	<0.2	0.21	<5	35	5	0.73	1	13	77	22	2.86	<10	0.73	360	3	0.01	19	360	14	10	<20	29	0.04	<10	3	<10	<1	39
62	B323720	<0.2	0.19	<5	25	<5	2.44	<1	10	118	21	2.29	<10	0.62	539	1	0.02	16	350	12	5	<20	103	0.03	<10	4	<10	<1	75
63	B323721	0.2	0.22	<5	35	<5	1.70	2	17	71	36	4.01	<10	0.60	357	3	0.01	31	530	14	15	<20	94	0.05	<10	4	<10	<1	31
64	B323722	0.2	0.26	20	30	<5	2.45	1	17	113	22	2.90	<10	0.66	432	2	0.01	28	500	14	10	<20	146	0.04	<10	5	<10	2	15
65	B323723	0.3	0.99	25	40	<5	0.62	<1	17	76	29	3.45	10	0.77	429	2	0.01	30	420	28	10	<20	27	0.05	<10	8	<10	<1	70
66	B323724	<0.2	1.01	15	40	<5	0.72	<1	16	90	25	3.28	20	0.77	536	2	0.01	29	430	34	5	<20	28	0.04	<10	8	<10	<1	74
67	B323725	0.3	1.23	5	40	5	1.05	1	18	86	29	3.36	<10	0.86	529	3	0.02	32	360	20	10	<20	49	0.05	<10	11	<10	<1	62
68	B323726	<0.2	1.18	<5	35	<5	0.94	1	18	108	29	3.41	<10	0.86	683	3	0.02	30	330	24	15	<20	48	0.05	<10	11	<10	<1	58
69	B323727	<0.2	1.04	15	40	<5	0.77	<1	17	121	37	3.18	10	0.84	417	4	0.01	32	410	16	15	<20	40	0.04	<10	10	<10	<1	54
70	B323728	<0.2	0.31	40	35	<5	1.05	1	17	103	33	3.45	10	0.92	577	3	0.02	32	370	16	15	<20	51	0.04	<10	5	<10	<1	49

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
71	B323729	0.3	0.24	55	40	<5	2.29	<1	15	116	24	3.30	<10	0.84	711	2	0.02	26	300	18	10	<20	130	0.05	<10	4	<10	<1	36
72	B323730	<0.2	0.26	35	35	<5	1.30	<1	13	84	24	3.02	20	0.78	505	2	0.02	24	420	8	10	<20	56	0.04	<10	4	<10	<1	75
73	B323731	<0.2	0.32	15	25	5	1.55	<1	11	97	14	2.57	10	0.74	577	1	0.02	17	400	10	<5	<20	67	0.04	<10	4	<10	<1	45
74	B323732	<0.2	0.35	15	40	<5	1.17	1	14	78	41	3.24	30	0.81	445	2	0.02	24	430	12	10	<20	58	0.04	<10	4	<10	1	74
75	B323733	0.4	0.63	15	45	<5	1.65	1	17	67	48	4.11	<10	1.01	1017	2	0.01	29	380	26	10	<20	140	0.05	<10	6	<10	1	54
76	B323734	<0.2	1.16	10	45	<5	0.93	<1	15	77	24	3.29	20	0.79	515	2	0.02	28	450	44	5	<20	64	0.05	<10	10	<10	<1	74
77	B323735	0.2	1.31	<5	40	<5	0.42	1	16	101	26	3.51	20	0.84	452	5	0.02	31	430	66	15	<20	23	0.04	<10	11	<10	<1	75
78	B323736	0.2	0.23	10	40	<5	0.60	2	14	89	22	3.12	20	0.78	451	4	0.02	23	360	20	15	<20	23	0.03	<10	4	<10	<1	52
79	B323737	<0.2	0.19	5	30	<5	0.78	<1	7	104	12	1.75	10	0.45	376	<1	0.02	9	330	20	<5	<20	35	0.03	<10	3	<10	<1	25
80	B323738	<0.2	0.26	<5	30	<5	0.64	<1	10	125	25	2.19	<10	0.49	240	<1	0.02	14	280	28	<5	<20	32	0.04	<10	3	<10	<1	39
81	B323739	<0.2	0.21	185	30	5	1.93	<1	21	83	23	4.39	<10	0.76	566	1	0.02	32	170	28	<5	<20	165	0.06	<10	4	<10	<1	52
82	B323740	1.0	0.24	230	40	5	1.76	<1	30	41	41	5.49	<10	0.78	482	4	0.01	53	110	30	20	<20	155	0.06	<10	4	<10	<1	77
83	B323741	1.0	0.23	150	35	5	1.75	<1	23	79	14	4.42	<10	0.56	437	1	0.02	38	110	28	<5	<20	138	0.05	<10	4	<10	<1	36
84	B323742	0.5	1.42	10	30	<5	1.49	2	24	84	43	3.97	<10	1.20	591	6	0.01	39	390	36	35	<20	91	0.04	<10	12	<10	<1	55
85	B323743	0.2	0.40	15	40	<5	0.48	<1	18	84	11	2.31	<10	0.31	250	<1	0.01	22	380	20	<5	<20	18	0.04	<10	4	<10	<1	14
86	B323744	0.2	1.42	<5	35	<5	3.37	2	21	129	65	3.76	<10	1.94	874	6	0.03	35	1310	26	30	<20	249	0.05	<10	72	<10	2	58
87	B323745	0.2	0.64	<5	40	<5	1.61	<1	12	90	24	2.23	<10	0.63	587	4	0.01	21	370	12	10	<20	57	0.03	<10	6	<10	2	26
88	B323746	<0.2	0.47	<5	25	<5	1.72	<1	12	73	20	2.09	<10	0.57	543	3	0.01	17	300	10	10	<20	56	0.03	<10	4	<10	2	22
89	B323747	<0.2	0.39	<5	30	<5	1.64	<1	13	110	28	2.37	<10	0.52	586	<1	0.01	15	320	22	<5	<20	57	0.06	<10	3	<10	<1	18
90	B323748	<0.2	2.35	<5	50	<5	8.19	3	50	268	81	6.72	<10	3.54	1245	10	0.02	175	910	32	45	<20	240	0.08	<10	141	<10	<1	76
91	B323749	<0.2	1.23	<5	50	<5	0.57	<1	14	80	29	2.92	20	0.66	439	2	0.01	25	550	42	<5	<20	22	0.04	<10	10	<10	<1	60
92	B323750	<0.2	1.26	<5	55	<5	0.25	<1	15	67	25	3.13	40	0.63	372	<1	0.01	26	600	28	<5	<20	<1	0.05	<10	10	<10	<1	68
93	B323717	>30	0.07	645	20	15	0.11	2	13	195	152	5.79	<10	<0.01	136	6	0.02	37	80	2694	25	<20	10	0.04	<10	5	<10	<1	1416
94	B323718	<0.2	0.05	10	5	<5	1.05	<1	4	161	9	1.21	<10	0.15	245	<1	0.02	10	250	16	<5	<20	48	0.03	<10	7	<10	2	14
95	B323719	0.2	0.03	15	10	5	0.04	2	5	209	4	3.13	<10	0.02	395	4	0.01	22	<10	10	15	<20	<1	0.02	<10	5	<10	<1	26
96	B315219	<0.2	0.06	5	10	<5	0.32	<1	2	304	4	0.55	<10	<0.01	77	<1	0.03	7	<10	<2	<5	<20	16	0.01	<10	2	<10	<1	<1
97	B315220	<0.2	0.13	35	25	<5	1.01	<1	3	200	3	0.95	<10	0.19	205	<1	0.02	5	90	4	<5	<20	62	0.02	<10	3	<10	1	3
98	B315221	0.2	0.10	20	15	<5	2.21	1	5	172	11	1.84	<10	0.62	336	2	0.02	12	20	8	15	<20	183	0.02	<10	3	<10	2	28
99	B315222	<0.2	0.08	10	10	<5	0.02	<1	4	231	10	0.77	<10	<0.01	102	2	0.01	13	40	8	5	<20	3	0.02	<10	1	<10	<1	6

QC DATA:

Repeat:

1	B324338	<0.2	0.28	10	30	<5	0.75	<1	11	138	15	2.16	<10	0.21	298	2	0.03	15	1070	6	<5	<20	43	0.03	<10	7	<10	2	18
10	B324347	<0.2	0.36	<5	35	<5	1.15	<1	11	119	11	1.82	<10	0.42	352	1	0.02	11	300	10	<5	<20	54	0.03	<10	5	<10	1	18
19	B324356	0.9	0.25	<5	80	<5	0.85	2	10	144	21	2.90	<10	0.69	373	4	0.02	22	290	14	10	<20	49	0.03	<10	4	<10	<1	40
36	B324373	<0.2	0.18	<5	25	<5	0.85	<1	8	129	13	2.18	<10	0.47	340	1	0.02	14	210	12	<5	<20	41	0.03	<10	3	<10	<1	30
45	B324382	0.2	0.26	45	40	<5	0.97	<1	13	82	28	1.90	<10	0.60	343	1	0.02	21	360	12	10	<20	65	0.03	<10	3	<10	2	13
54	B324391	0.5	0.29	225	40	<5	0.81	<1	25	27	18	2.91	<10	0.19	118	<1	0.01	36	880	56	<5	<20	55	0.04	<10	3	<10	2	7
71	B323729	0.3	0.26	60	45	<5	2.35	1	15	122	25	3.38	<10	0.87	728	3	0.02	28	310	16	15	<20	134	0.04	<10	4	<10	<1	35
80	B323738	<0.2	0.26	5	30	<5	0.62	<1	10	130	25	2.16	<10	0.49	237	1	0.02	16	270	30	<5	<20	34	0.03	<10	3	<10	<1	41
89	B323747	<0.2	0.39	<5	30	5	1.61	1	13	114	27	2.33	<10	0.54	576	3	0.01	17	320	20	10	<20	56	0.04	<10	5	<10	1	18

Resplit:

1	B324338	<0.2	0.29	5	30	<5	0.84	<1	12	133	14	2.34	<10	0.22	312	1	0.03	15	1180	6	<5	<20	51	0.04	<10	7	<10	2	15
36	B324373	<0.2	0.19	<5	30	<5	0.97	<1	8	121	14	2.41	<10	0.55	391	<1	0.02	15	200	14	<5	<20	41	0.05	<10	3	<10	<1	33
71	B323729	0.3	0.24	50	40	5	2.25	<1	16	105	26	3.36	<10	0.86	735	2	0.01	26	320	16	10	<20	123	0.05	<10	4	<10	1	33

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
Standard:																													
Pb129a		11.5	0.82	<5	50	<5	0.47	51	6	11	1410	1.57	<10	0.66	352	3	0.03	7	430	6164	60	<20	22	0.03	<10	19	<10	<1	9927
Pb129a		12.4	0.86	<5	60	<5	0.50	52	6	11	1404	1.57	<10	0.68	362	3	0.03	8	430	6230	55	<20	24	0.03	<10	19	<10	<1	9900
Pb129a		11.8	0.88	<5	60	<5	0.50	52	7	11	1414	1.52	<10	0.70	365	2	0.03	9	430	6218	60	<20	27	0.02	<10	19	<10	<1	9997



JJ/nw
df/1059s
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

HOLES PLOTTED


TOTAL 3

08MER00 08MER01 08MER02



ROCK CODES	PAT	LABEL	DESCRIPTION
Rock		ARG	ARGILLITE
		ARGMX	ARG > QP
		FZ	FAULT ZONE
		MX	50:50 QP:ARG
		OB	overburden
		QP	quartz pelite
		QPMX	quartz pelite domintate
		QSAD	quartz SAD vn
		QVN	quartz vn



SECTION SPECS:
 REF. PT. E, N 455818 m 5627610 m
 EXTENTS 400.2 m 202.9 m
 SECTION TOP, BOT 975 m 772.1 m
 TOLERANCE +/- 14.4 m



HOLES PLOTTED

TOTAL 3


08MER00 08MER01 08MER02



ASSAYS	L/R	TEXT
Au (g/t)	R	---

SECTION SPECS:

REF. PT. E, N	455822 m	5627610 m
EXTENTS	443.8 m	225.1 m
SECTION TOP, BOT	1000 m	774.9 m
TOLERANCE +/-	50 m	





MANSON CREEK RESOURCES LTD
MERIDIAN
2008 MERIDIAN DRILL PROGRAM
Section 08MER-00 to 02

HOLES PLOTTED

TOTAL 3


08MER00 08MER01 08MER02



ASSAYS	L/R	TEXT
Ag	R	-----

SECTION SPECS:



REF. PT. E, N	455821 m	5627610 m
EXTENTS	493 m	250 m
SECTION TOP, BOT	1000 m	750 m
TOLERANCE +/-	20.1 m	



HOLES PLOTTED

TOTAL 1



08MER03



ROCK CODES	PAT	LABEL	DESCRIPTION
Rock		ARG	ARGILLITE
		ARGMX	ARG > QP
		FZ	FAULT ZONE
		GRT	GRANITE
		MX	50:50 QP:ARG
		OB	overburden
		QP	quartz pelite
		QPMX	quartz pelite dominant
		QSAD	quartz SAD vn

SECTION SPECS:



REF. PT. E, N 455869 m 5627530 m
 EXTENTS 400.2 m 202.9 m
 SECTION TOP, BOT 1050 m 847.1 m
 TOLERANCE +/- 18.05 m




HOLES PLOTTED

TOTAL 1

08MER03





ASSAYS	L/R	TEXT
Au (g/t)	R	---
SECTION SPECS:		
REF. PT. E, N	455879 m	5627540 m
EXTENTS	400.2 m	202.9 m
SECTION TOP, BOT	1050 m	847.1 m
TOLERANCE +/-	25 m	



HOLES PLOTTED

TOTAL 1


08MER03



ASSAYS	L/R	TEXT
Ag	R	---

SECTION SPECS:



REF. PT. E, N	455883 m	5627540 m
EXTENTS	443.8 m	225.1 m
SECTION TOP, BOT	1050 m	824.9 m
TOLERANCE +/-	10.55 m	



HOLES PLOTTED



TOTAL 1

08MER04



ROCK CODES	PAT	LABEL	DESCRIPTION
Rock			
ARG	[Pattern]	ARG	ARGILLITE
ARGMX	[Pattern]	ARGMX	ARG > QP
FZ	[Pattern]	FZ	FAULT ZONE
MX	[Pattern]	MX	50:50 QP:ARG
OB	[Pattern]	OB	overburden
PSAM	[Pattern]	PSAM	psammite
QP	[Pattern]	QP	quartz pelite
QPMX	[Pattern]	QPMX	quartz pelite domintate
QSAD	[Pattern]	QSAD	quartz SAD vn
QVN	[Pattern]	QVN	quartz vn



SECTION SPECS:
 REF. PT. E, N 456182 m 5627100 m
 EXTENTS 400.2 m 202.9 m
 SECTION TOP, BOT 1150 m 947.1 m
 TOLERANCE +/- 17 m




HOLES PLOTTED

TOTAL 1

08MER04



ASSAYS	L/R	TEXT
Au (g/t)	R	---
SECTION SPECS:		
REF. PT. E, N	456187 m	5627100 m
EXTENTS	493 m	250 m
SECTION TOP, BOT	1150 m	900 m
TOLERANCE +/-	25 m	





MANSON CREEK RESOURCES LTD
 MERIDIAN
 2008 MERIDIAN DRILL PROGRAM
 Section 08MER-04

HOLES PLOTTED

TOTAL 1


08MER04



ASSAYS	L/R	TEXT
Ag	R	---

SECTION SPECS:

REF. PT. E, N	456182 m	5627100 m
EXTENTS	400.2 m	202.9 m
SECTION TOP, BOT	1150 m	947.1 m
TOLERANCE +/-	17 m	





MANSON CREEK RESOURCES LTD
MERIDIAN
2008 MERIDIAN DRILL PROGRAM
Section 08MER-04

HOLES PLOTTED

TOTAL 2



08MER05 08MER06



ROCK CODES	PAT	LABEL	DESCRIPTION
Rock	ARG	ARG	ARGILLITE
	FZ	FZ	FAULT ZONE
	MSV	MSV	MASSIVE SULPHIDES
	MX	MX	50:50 QP:ARG
	OB	OB	overburden
	PSAM	PSAM	psammitic
	QP	QP	quartz pelite
	QSAD	QSAD	quartz SAD vn
	QVN	QVN	quartz vn

SECTION SPECS:



REF. PT. E, N 455961 m 5627140 m
 EXTENTS 400.2 m 202.9 m
 SECTION TOP, BOT 1050 m 847.1 m
 TOLERANCE +/- 21.95 m




HOLES PLOTTED

TOTAL 2

08MER05 08MER06





ASSAYS	L/R	TEXT
Au (g/t)	R	---
SECTION SPECS:		
REF. PT. E, N	455965 m	5627140 m
EXTENTS	493 m	250 m
SECTION TOP, BOT	1050 m	800 m
TOLERANCE +/-	29.5 m	





HOLES PLOTTED

TOTAL 2

08MER05 08MER06



ASSAYS	L/R	TEXT
Ag	R	---
SECTION SPECS:		
REF. PT. E, N	455963 m	5627140 m
EXTENTS	400.2 m	202.9 m
SECTION TOP, BOT	1050 m	847.1 m
TOLERANCE +/-	15 m	



MANSON CREEK RESOURCES LTD
MERIDIAN
2008 MERIDIAN DRILL PROGRAM
Section 08MER-05 and 06