

Diamond Drilling, Prospecting and Surface Sampling Assessment Report

On The

**BC Geological Survey
Assessment Report
31000b**

Dilworth Property

Stewart, BC

VOLUME II

APPENDIX I – Analytical Data

APPENDIX J – SAMPLE DESCRIPTIONS

APPENDIX K – ANALYTICAL CERTIFICATES

For

Ascot Resources Ltd.

Suite 420 – 475 Howe St. Vancouver BC, V6C 2B3

By

Susan Deane, B. Sc. and Warner Gruenwald, P. Geo.

May 2009

APPENDIX I

**ANALYTICAL DATA – DRILLING, SURFACE SAMPLING, SOILS, STREAM SEDIMENTS, STANDARDS
AND BLANKS**

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Int (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0					Ag: 5-10 10-50 50-100 >100					Pb/Zn: 2500-5000 5000-10000 >10000																								
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
H08-01 - Zone: Chicago North, Pad 12: 435176E, 6224204N, Elev: 1220m, Az: 247, Dip: -50, EOH: 261.28m																																								
8V2229RA/RJ	HL08-01	48701	0.00	5.00	5.00	0.03	2.4	1.64	58	139	<0.5	11	0.77	2	12	20	<1	4.47	<1	0.18	<10	0.73	947	<2	0.01	6	980	<2	1.42	<5	2	21	<5	<0.01	<10	<10	33	<10	81	3
8V2229RA/RJ	HL08-01	48702	5.00	7.00	2.00	0.10	18.0	1.52	91	124	<0.5	12	0.52	2	9	19	9	4.04	<1	0.19	<10	0.65	755	<2	0.01	3	944	37	1.35	<5	2	9	<5	<0.01	<10	<10	33	<10	162	2
8V2229RA/RJ	HL08-01	48703	7.00	9.00	2.00	0.01	16.0	1.78	22	128	<0.5	11	0.59	1	10	21	<1	4.17	<1	0.18	<10	0.78	990	<2	0.01	1	1028	<2	0.75	<5	2	13	<5	<0.01	<10	<10	39	<10	87	3
8V2229RA/RJ	HL08-01	48704	9.00	10.50	1.50	0.05	2.7	1.41	63	181	<0.5	5	0.66	1	11	21	1	3.79	1	0.18	<10	0.58	785	<2	0.01	2	938	4	1.26	5	2	17	<5	<0.01	<10	<10	29	<10	69	2
8V2229RA/RJ	HL08-01	48705	10.50	12.00	1.50	0.05	2.0	1.58	44	104	<0.5	8	0.74	2	10	28	8	3.99	<1	0.16	<10	0.67	955	<2	0.01	3	957	<2	0.93	<5	2	14	<5	<0.01	<10	<10	36	<10	67	2
8V2229RA/RJ	HL08-01	48706	12.00	13.00	1.00	0.09	2.4	1.37	85	147	<0.5	11	0.47	1	11	24	29	3.75	1	0.20	<11	0.54	862	<2	0.01	3	848	7	1.30	<5	2	7	5	<0.01	<10	<11	25	<10	61	3
8V2229RA/RJ	HL08-01	48707	13.00	15.00	2.00	<0.01	1.2	1.79	18	142	<0.5	7	0.83	1	11	18	13	3.98	<1	0.20	<14	0.67	943	<2	0.02	3	3284	<2	0.53	<5	2	18	<5	<0.01	<10	<14	29	<10	73	3
8V2229RA/RJ	HL08-01	48708	15.00	17.00	2.00	0.01	0.9	1.69	23	142	<0.5	7	0.36	1	11	17	<1	4.17	<1	0.20	<10	0.64	1012	<2	0.02	2	815	<2	0.90	<5	2	3	<5	<0.01	<10	<10	29	<10	80	2
8V2229RA/RJ	HL08-01	48709	17.00	19.00	2.00	0.04	2.1	1.38	84	135	<0.5	11	0.37	2	9	37	3	4.03	<1	0.17	<10	0.49	835	<2	0.02	3	606	2	1.50	<5	2	5	<5	<0.01	<10	<10	23	<10	57	2
8V2229RA/RJ	HL08-01	48710	19.00	21.00	2.00	0.11	3.0	1.74	94	145	<0.5	11	0.39	2	13	20	20	4.42	<1	0.21	<11	0.69	1023	<2	0.02	4	1026	5	1.24	<5	2	5	<5	<0.01	<10	<11	32	<10	87	3
8V2229RA/RJ	HL08-01	48711	21.00	23.00	2.00	0.07	3.4	1.82	90	119	<0.5	11	0.63	2	13	21	15	4.63	<1	0.18	<10	0.75	1199	<2	0.02	3	1375	<2	1.09	5	3	11	<5	<0.01	<10	<10	45	<10	76	3
8V2229RA/RJ	HL08-01	48712	23.00	25.00	2.00	0.02	1.5	2.28	11	130	<0.5	8	0.63	2	14	17	18	4.86	<1	0.19	<10	1.06	1626	<2	0.02	3	633	<2	0.34	<5	3	17	<5	<0.01	<10	<10	54	<10	79	3
8V2229RA/RJ	HL08-01	48713	25.00	27.00	2.00	0.07	2.0	1.92	39	147	<0.5	13	0.45	2	12	26	7	4.62	<1	0.20	<10	0.86	1268	<2	0.02	2	661	3	1.02	<5	2	9	<5	<0.01	<10	<10	40	<10	71	3
8V2229RA/RJ	HL08-01	48714	27.00	29.00	2.00	0.27	3.5	1.52	35	157	<0.5	7	0.67	2	10	27	3	3.90	<1	0.23	<10	0.59	1102	<2	0.01	2	477	15	1.14	<5	2	20	<5	<0.01	<10	<10	26	<10	84	3
8V2229RA/RJ	HL08-01	48715	29.00	31.00	2.00	0.14	0.9	1.65	15	134	<0.5	6	0.72	1	10	30	<1	3.85	1	0.20	<10	0.65	1114	<2	0.01	3	559	<2	0.67	<5	2	21	<5	<0.01	<10	<10	30	<10	64	3
8V2229RA/RJ	HL08-01	48716	31.00	32.50	1.50	0.23	3.2	1.00	105	140	<0.5	6	0.33	1	9	28	<1	3.25	1	0.22	<10	0.33	536	<2	0.01	2	479	9	1.75	5	2	5	<5	<0.01	<10	<10	19	<10	47	3
8V2229RA/RJ	HL08-01	48717	32.50	33.50	1.00	0.09	2.6	0.93	91	158	<0.5	10	0.62	1	10	49	<1	3.31	1	0.18	<10	0.33	628	<2	0.01	3	566	1.85	<5	2	19	<5	<0.01	<10	<10	16	<10	51	2	
8V2229RA/RJ	HL08-01	48718	33.50	34.00	0.50	0.51	22.1	1.31	88	114	<0.5	13	2.63	6	14	48	9	4.83	<1	0.21	<11	0.58	1354	<2	0.01	5	1111	304	2.76	5	3	103	<5	0.01	<10	<11	26	<10	575	3
8V2229RA/RJ	HL08-01	48719	34.00	36.00	2.00	0.19	2.7	1.85	120	126	<0.5	6	2.03	2	14	18	51	5.62	<1	0.20	<11	0.87	1592	<2	0.01	4	1283	17	2.44	10	3	49	<5	0.03	<10	<11	33	<10	153	3
8V2229RA/RJ	HL08-01	48720	Blank	Blank		0.01	0.2	1.02	<5	235	<0.5	5	0.50	1	6	119	<1	2.07	2	0.46	<10	0.60	565	<2	0.06	5	725	<2	0.03	<5	2	43	5	0.13	<10	<10	39	<10	51	2
8V2229RA/RJ	HL08-01	48721	Std	PM1110		1.68	181.0	0.88	217	210	<0.5	104	5.56	2	17	22	4196	3.77	5	0.17	<10	0.20	640	76	0.03	36	601	218	1.45	288	2	198	<5	0.06	<10	<10	23	27	254	9
8V2229RA/RJ	HL08-01	48722	36.00	38.00	2.00	0.45	7.5	1.97	74	130	<0.5	14	5.10	2	15	15	42	5.03	<1	0.22	<10	1.03	2595	<2	0.01	3	1263	16	1.55	<5	3	143	<5	0.01	<10	<10	33	<10	115	3
8V2229RA/RJ	HL08-01	48723	38.00	40.00	2.00	<0.01	2.2	2.29	60	166	<0.5	17	4.23	2	13	12	16	5.44	2	0.26	<12	1.21	2416	<2	0.02	5	1378	<2	1.32	<5	4	127	<5	0.01	<10	<12	36	<10	99	3
8V2229RA/RJ	HL08-01	48724	40.00	42.00	2.00	0.03	3.2	1.73	58	134	<0.5	14	2.68	2	15	20	31	5.30	<1	0.23	<10	0.90	1539	<2	0.01	3	1417	7	2.65	8	3	83	<5	<0.01	<10	<10	27	<10	91	3
8V2229RA/RJ	HL08-01	48725	42.00	44.00	2.00	0.03	1.7	2.14	63	197	<0.5	<5	2.75	1	17	9	13	4.66	<1	0.27	13	1.18	1489	<2	0.02	6	1293	6	1.08	<5	4	94	<5	<0.01	<10	<10	39	<10	100	3
8V2229RA/RJ	HL08-01	48726	44.00	46.00	2.00	0.03	1.2	1.61	48	176	<0.5	<5	2.38	1	13	12	<1	3.44	<1	0.27	<11	0.83	1390	<2	0.02	5	1152	7	0.80	<5	3	72	<5	<0.01	<10	<10	28	<10	66	2
8V2229RA/RJ	HL08-01	48727	46.00	48.00	2.00	0.14	4.4	1.75	93	148	<0.5	<5	1.88	1	16	9	28	4.86	<1	0.29	<12	0.89	1413	<2	0.02	6	1244	9	2.13	<5	3	66	<5	<0.01	<10	<10	33	<10	86	3
8V2229RA/RJ	HL08-01	48728	48.00	50.00	2.00	0.12	4.0	1.52	93	131	<0.5	<5	1.56	1	16	12	23	4.76	<1	0.29	<11	0.73	1229	<2	0.02	5	1030	10	2.56	<5	2	56	<5	0.01	<10	<10	28	<10	65	3
8V2229RA/RJ	HL08-01	48729	50.00	52.00	2.00	0.17	3.3	1.42	96	126	<0.5	<5	1.14	1	14	10	24	4.37	<1	0.36	<10	0.65	1013	<2	0.02	4	1236	19	2.37	<5	3	50	<5	<0.01	<10	<10	26	<10	71	3
8V2229RA/RJ	HL08-01	48730	52.00	54.00	2.00	0.23	3.0	1.41	85	193	<0.5	<5	1.69	1	13	8	12	3.49	<1	0.30	<10	0.66	1051	<2	0.02	4	1168	8	1.26	<5	2	61	<5	<0.01	<10	<10	20	<10	70	2

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0					Ag: 5-10 10-50 50-100 >100					Pb/Zn: 2500-5000 5000-10000 >10000																								
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V2278RA/RJ	HL08-01	48771	130.00	132.00	2.00	<0.01	1.5	2.06	10	125	<0.5	10	3.67	2	32	1	80	4.32	<1	0.24	<10	1.14	3122	<2	0.02	4	951	4	0.27	<5	3	101	<5	0.01	<10	<10	55	<10	73	2
8V2278RA/RJ	HL08-01	48772	132.00	133.40	1.40	0.01	1.7	2.20	8	127	<0.5	9	2.25	2	32	1	103	4.82	<1	0.22	<10	1.23	2820	<2	0.02	5	1189	3	0.39	7	3	65	<5	0.01	<10	<10	63	<10	88	3
8V2278RA/RJ	HL08-01	48773	133.40	134.30	0.90	0.05	2.6	1.18	117	76	<0.5	7	0.96	2	28	8	51	5.07	<1	0.23	<10	0.55	1309	<2	0.01	4	803	14	3.46	<5	2	38	<5	0.01	<10	<10	64	<10	46	3
8V2278RA/RJ	HL08-01	48774	134.30	134.75	0.45	0.10	5.6	2.45	282	37	<0.5	18	1.33	5	25	14	87	10.78	<1	0.11	<10	1.20	3129	<2	0.01	4	752	35	>50.00	8	3	61	<5	0.01	<10	<10	129	<10	74	6
8V2278RA/RJ	HL08-01	48775	134.75	137.00	2.25	0.01	2.8	1.84	84	148	<0.5	9	2.96	2	23	2	84	4.63	<1	0.26	<10	0.96	2431	<2	0.01	4	1069	5	1.08	7	3	81	<5	0.02	<10	<10	45	<10	63	3
8V2278RA/RJ	HL08-01	48776	Blank	Blank		<0.01	<0.2	0.81	<5	197	<0.5	<5	0.35	<1	5	89	1	1.72	<1	0.43	<10	0.52	475	<2	0.06	6	715	<2	0.01	<5	2	33	5	0.10	<10	<10	31	<10	39	2
8V2278RA/RJ	HL08-01	48777	Std	PM11110		1.79	144.5	0.51	200	124	<0.5	87	3.45	2	14	15	3420	2.47	3	0.13	<10	0.16	408	72	0.02	29	550	194	1.10	271	1	139	<5	0.03	<10	<10	14	26	204	5
8V2278RA/RJ	HL08-01	48778	137.00	139.00	2.00	0.06	12.7	2.00	72	128	<0.5	14	3.43	2	20	11	88	4.77	<1	0.23	<10	1.15	2770	<2	0.01	4	959	68	0.92	<5	3	88	<5	0.02	<10	<10	52	<10	94	3
8V2278RA/RJ	HL08-01	48779	139.00	141.00	2.00	0.03	2.1	2.02	8	135	<0.5	7	3.40	2	18	6	96	4.21	<1	0.24	<10	1.27	2553	<2	0.02	3	1123	18	0.35	<5	3	108	<5	0.02	<10	<10	54	<10	69	2
8V2278RA/RJ	HL08-01	48780	141.00	143.00	2.00	0.01	2.2	2.03	16	132	<0.5	11	3.03	2	17	7	83	4.48	<1	0.25	<10	1.32	2702	<2	0.02	3	1060	10	0.70	<5	3	104	<5	0.02	<10	<10	53	<10	67	2
8V2278RA/RJ	HL08-01	48781	143.00	145.00	2.00	0.02	2.2	1.79	30	122	<0.5	10	2.72	1	18	3	96	3.79	<1	0.24	<10	1.21	2576	<2	0.02	4	1074	6	0.56	<5	3	83	<5	0.01	<10	<10	49	<10	72	2
8V2278RA/RJ	HL08-01	48782	145.00	147.00	2.00	0.03	2.3	1.76	55	207	<0.5	10	3.21	2	19	23	33	4.39	<1	0.23	14	1.33	2048	<2	0.02	7	1778	23	0.90	<5	4	137	<5	<0.01	<10	14	54	<10	126	3
8V2278RA/RJ	HL08-01	48783	147.00	149.00	2.00	0.03	8.1	1.92	49	126	<0.5	11	1.67	2	30	5	100	5.04	<1	0.26	<10	1.12	2832	<2	0.01	5	1314	10	1.44	<5	3	83	<5	<0.01	<10	<10	45	<10	81	3
8V2278RA/RJ	HL08-01	48784	149.00	151.00	2.00	0.03	3.4	1.67	45	158	<0.5	9	1.48	2	23	6	69	4.50	<1	0.27	<10	0.76	2305	<2	0.01	1	1488	6	0.75	6	3	64	<5	0.01	<10	<10	36	<10	79	3
8V2278RA/RJ	HL08-01	48785	151.00	153.00	2.00	0.01	1.9	1.42	38	211	<0.5	9	1.71	1	22	3	33	4.10	<1	0.28	<10	0.61	2025	<2	0.02	2	1770	6	0.70	6	3	86	<5	0.01	<10	<10	32	<10	70	3
8V2278RA/RJ	HL08-01	48786	153.00	155.00	2.00	0.01	0.6	1.28	7	424	<0.5	8	1.69	1	22	5	21	3.57	<1	0.29	<10	0.54	2017	<2	0.01	1	1753	2	0.10	6	3	92	<5	0.01	<10	<10	32	<10	61	3
8V2278RA/RJ	HL08-01	48787	155.00	157.00	2.00	0.01	1.1	1.26	72	266	<0.5	8	1.37	1	27	3	62	3.77	<1	0.30	<10	0.54	1766	<2	0.01	2	1496	2	0.45	6	3	74	<5	0.01	<10	<10	36	<10	66	3
8V2278RA/RJ	HL08-01	48788	157.00	159.00	2.00	0.01	0.7	1.45	<5	596	<0.5	8	2.14	2	27	2	64	4.52	1	0.30	<10	0.61	1875	<2	0.02	4	1424	11	0.05	7	3	117	<5	0.03	<10	<10	53	<10	84	4
8V2278RA/RJ	HL08-01	48789	159.00	160.40	1.40	<0.01	1.1	1.45	<5	459	<0.5	<5	2.00	2	24	2	89	4.33	<1	0.24	<10	0.64	1836	<2	0.01	3	1408	8	0.08	7	3	90	<5	0.02	<10	<10	42	<10	82	3
8V2278RA/RJ	HL08-01	48790	160.40	162.00	1.60	0.01	2.4	1.31	53	322	<0.5	<5	1.17	1	25	<1	43	3.40	<1	0.25	<10	0.57	1122	<2	0.01	4	1498	8	0.50	<5	3	64	<5	<0.01	<10	<10	30	<10	74	2
8V2278RA/RJ	HL08-01	48791	162.00	164.00	2.00	<0.01	3.3	1.77	32	172	<0.5	7	2.36	2	23	1	94	4.14	<1	0.25	<10	0.88	1865	<2	0.01	4	1535	8	0.41	8	3	104	<5	<0.01	<10	<10	37	<10	74	2
8V2278RA/RJ	HL08-01	48792	164.00	166.00	2.00	0.01	2.8	2.08	<5	159	<0.5	6	3.27	2	22	1	260	4.64	<1	0.25	<10	1.21	2353	<2	0.01	6	1401	9	0.06	<5	5	144	<5	<0.01	<10	<10	42	<10	71	3
8V2278RA/RJ	HL08-01	48793	166.00	168.00	2.00	<0.01	1.7	2.34	<5	133	<0.5	7	2.52	2	24	2	50	5.56	<1	0.27	10	1.63	2217	<2	0.01	9	1666	11	0.02	<5	5	123	<5	<0.01	<10	<10	49	<10	104	3
8V2278RA/RJ	HL08-01	48794	168.00	170.00	2.00	0.01	3.1	2.54	<5	122	<0.5	8	6.06	2	25	1	113	5.59	1	0.26	<10	1.49	3479	<2	0.01	7	1492	10	0.24	6	5	545	<5	<0.01	<10	<10	51	<10	135	3
8V2278RA/RJ	HL08-01	48795	170.00	172.00	2.00	0.01	4.4	1.64	82	161	<0.5	5	3.32	2	25	6	79	4.48	<1	0.27	<10	0.84	2083	<2	0.01	5	1528	11	0.98	<5	4	238	<5	<0.01	<10	<10	33	<10	91	3
8V2278RA/RJ	HL08-01	48796	172.00	174.00	2.00	<0.01	2.2	1.91	6	520	<0.5	<5	2.59	2	16	15	86	4.33	<1	0.24	14	1.10	1430	<2	0.02	5	1761	30	0.19	<5	3	199	<5	<0.01	<10	14	43	<10	144	3
8V2278RA/RJ	HL08-01	48797	174.00	176.00	2.00	0.02	3.7	1.83	198	124	<0.5	9	1.42	3	31	5	95	5.12	2	0.24	<10	1.01	1666	<2	0.01	6	1546	40	1.60	7	3	73	<5	<0.01	<10	<10	45	<10	123	3
8V2278RA/RJ	HL08-01	48798	176.00	178.00	2.00	0.01	2.3	1.68	64	119	<0.5	8	2.66	2	20	6	55	4.28	<1	0.22	<10	1.00	2387	<2	0.01	5	1662	13	0.84	5	3	172	<5	<0.01	<10	<10	34	<10	80	2
8V2278RA/RJ	HL08-01	48799	178.00	180.00	2.00	0.09	4.6	1.15	172	111	<0.5	8	2.98	2	22	6	128	5.04	<1	0.25	<10	0.97	2214	<2	0.01	3	1548	18	2.10	7	4	155	<5	<0.01	<10	<10	30	<10	70	3
8V2278RA/RJ	HL08-01	48800	180.00	182.00	2.00	<0.01	2.7	1.14	148	121	<0.5	<5	4.41	2	19	15	65	3.84	<1	0.24	<10	0.81	2543	<2	0.02	3	1411	13	1.37	7	4	241	<5	<0.01	<10	<10	30	<10	57	2
8V2278RA/RJ	HL08-01	4																																						

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0					Ag: 5-10 10-50 50-100 >100					Pb/Zn: 2500-5000 5000-10000 >10000																									
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th %	Ti ppm	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
HL08-02 - Zone: Chicago North, Pad 12: 435176E, 6224204N, Elev: 1220m, Az: 218, Dip: -45, EOH: 56.71m																																								
No Samples																																								
HL08-03 - Zone: 49er, Pad 13: 4351119E, 6223470N, Elev: 1203m, Az: 222, Dip: -50, EOH: 239.94m																																								
8V2278RA/RJ	HL08-03	48843	2.88	5.00	2.12	0.25	4.2	0.43	305	95	<0.5	5	0.32	3	11	12	48	3.48	<1	0.21	<10	0.10	318	5	0.01	2	948	87	2.41	10	1	19	<5	<0.01	<10	<10	11	<10	258	2
8V2278RA/RJ	HL08-03	48844	5.00	7.00	2.00	0.04	2.8	0.64	72	97	<0.5	6	0.30	2	11	6	116	3.48	<1	0.24	<10	0.31	594	7	0.01	2	1124	28	2.07	7	1	12	<5	<0.01	<10	<10	18	<10	226	2
8V2278RA/RJ	HL08-03	48845	7.00	9.00	2.00	0.08	2.1	0.73	105	96	<0.5	5	0.30	2	12	8	71	4.12	<1	0.25	<10	0.33	517	5	0.01	2	1137	20	2.97	7	1	13	<5	<0.01	<10	<10	19	<10	63	2
8V2278RA/RJ	HL08-03	48846	9.00	11.00	2.00	0.05	1.7	1.14	62	120	<0.5	11	0.41	2	12	8	56	4.08	<1	0.26	10	0.56	899	10	0.01	2	1162	19	2.03	6	2	16	<5	<0.01	<10	<10	33	<10	130	2
8V2278RA/RJ	HL08-03	48847	11.00	13.00	2.00	0.14	1.1	1.65	35	143	<0.5	7	0.47	3	13	7	64	4.11	<1	0.28	10	0.89	1341	5	0.01	2	1287	106	0.72	10	2	29	<5	<0.01	<10	10	51	<10	213	2
8V2278RA/RJ	HL08-03	48848	13.00	15.00	2.00	0.10	1.8	1.76	47	146	<0.5	<5	0.64	8	13	10	98	4.35	<1	0.28	12	1.04	1513	7	0.01	3	1249	48	0.70	6	3	48	<5	<0.01	<10	12	52	<10	697	3
8V2278RA/RJ	HL08-03	48849	15.00	17.00	2.00	0.26	3.0	1.84	141	128	<0.5	8	1.03	3	15	6	174	4.85	<1	0.26	10	1.04	1595	13	0.02	3	1274	49	1.10	5	3	68	<5	<0.01	<10	10	63	<10	210	3
8V2278RA/RJ	HL08-03	48850	17.00	19.00	2.00	0.16	6.2	1.27	156	115	<0.5	5	0.46	4	13	9	90	4.44	<1	0.26	10	0.69	1094	9	0.01	3	1161	97	2.13	8	2	35	<5	<0.01	<10	10	36	<10	290	3
8V2278RA/RJ	HL08-03	48851	19.00	20.40	1.40	0.05	2.6	1.22	47	115	<0.5	6	0.38	3	14	7	86	4.16	<1	0.27	12	0.62	1004	5	0.01	3	1164	44	1.77	<5	2	24	<5	<0.01	<10	12	32	<10	187	2
8V2278RA/RJ	HL08-03	48852	20.40	21.40	1.00	0.74	6.8	0.39	386	59	<0.5	7	0.26	10	11	18	112	4.03	<1	0.20	<10	0.13	310	13	0.01	2	791	577	3.72	16	1	17	<5	<0.01	<10	<10	10	<10	1042	2
8V2278RA/RJ	HL08-03	48853	21.40	22.40	1.00	0.32	5.3	0.26	317	45	<0.5	6	0.41	11	13	<1	109	4.67	<1	0.12	<10	0.18	487	16	<0.01	2	963	276	4.17	12	1	26	<5	<0.01	<10	<10	9	<10	1013	2
8V2278RA/RJ	HL08-03	48854	22.40	23.40	1.00	0.40	6.1	0.36	367	84	<0.5	8	1.02	3	12	26	87	4.17	<1	0.26	<10	0.33	784	16	0.01	2	918	87	3.45	13	1	107	<5	<0.01	<10	<10	9	<10	277	2
8V2278RA/RJ	HL08-03	48855	23.40	24.60	1.20	0.34	15.5	0.35	685	77	<0.5	<5	0.46	9	11	19	89	4.11	<1	0.21	<10	0.12	378	30	0.01	2	784	273	3.48	28	1	21	<5	<0.01	<10	<10	10	<10	913	2
8V2278RA/RJ	HL08-03	48856	24.60	25.60	1.00	5.72	1162.0	0.14	1448	26	<0.5	15	0.95	176	5	73	669	7.74	<1	0.08	34	0.04	382	8	<0.01	2	158	8429	>5.00	143	<1	17	<5	<0.01	<10	35	7	<10	28100	4
8V2278RA/RJ	HL08-03	48857	25.60	26.60	1.00	1.61	1073.0	0.15	920	31	<0.5	<5	1.19	102	4	69	435	4.80	<1	0.07	34	0.05	496	13	<0.01	2	108	4687	>5.00	98	<1	18	<5	<0.01	<10	34	7	<10	15700	2
8V2278RA/RJ	HL08-03	48858	26.60	27.60	1.00	0.24	15.6	0.57	215	67	<0.5	8	1.53	10	12	37	60	4.07	<1	0.16	<10	0.29	868	20	0.01	2	812	671	3.13	12	1	56	<5	<0.01	<10	<10	24	<10	1209	2
8V2278RA/RJ	HL08-03	48859	27.60	29.60	2.00	0.75	26.6	1.57	189	108	<0.5	6	2.46	3	16	6	278	4.69	<1	0.27	<10	0.84	1575	16	0.01	2	1402	27	1.18	11	3	95	<5	<0.01	<10	<10	47	<10	292	2
8V2278RA/RJ	HL08-03	48860	Blank	Blank		0.02	<0.2	0.87	<5	217	<0.5	<5	0.42	1	6	62	3	1.79	<1	0.42	<10	0.53	500	<2	0.06	5	697	8	0.01	5	2	36	6	11	<10	<10	34	<10	42	2
8V2278RA/RJ	HL08-03	48861	Std	PM 1112		1.43	236.9	0.62	2030	82	<0.5	51	3.59	2	54	18	2226	2.66	<1	0.06	<10	0.21	717	141	0.04	21	819	362	0.59	521	1	131	<5	0.02	<10	<10	15	21	269	5
8V2278RA/RJ	HL08-03	48862	29.60	30.60	1.00	0.26	4.1	1.31	154	112	<0.5	6	5.65	2	13	6	254	3.93	<1	0.31	<10	0.64	1805	19	0.01	1	1261	23	1.40	<5	2	197	<5	<0.01	<10	<10	38	<10	184	2
8V2278RA/RJ	HL08-03	48863	30.60	32.60	2.00	0.47	3.1	1.73	68	193	<0.5	9	4.08	3	15	5	245	4.70	<1	0.39	<10	0.74	2026	93	0.01	1	1592	26	0.64	5	3	172	<5	<0.01	<10	<10	58	<10	242	2
8V2278RA/RJ	HL08-03	48864	32.60	34.60	2.00	0.69	3.5	1.48	135	126	0.5	6	2.87	3	20	2	331	4.78	<1	0.36	<10	0.58	1554	41	0.01	2	1747	42	1.50	10	4	96	<5	<0.01	<10	<10	40	<10	293	2
8V2278RA/RJ	HL08-03	48865	34.60	36.60	2.00	0.43	5.5	1.76	46	175	0.5	<5	2.56	4	18	2	610	4.60	<1	0.39	<10	0.77	1686	84	0.01	1	1520	29	0.74	<5	3	107	<5	<0.01	<10	<10	53	<10	321	3
8V2278RA/RJ	HL08-03	48866	36.60	38.60	2.00	0.26	4.1	1.78	30	168	0.6	<5	3.05	4	19	1	335	4.66	<1	0.37	<10	0.84	1749	14	0.01	3	1566	21	0.56	<5	3	137	<5	<0.01	<10	<10	50	<10	357	2
8V2278RA/RJ	HL08-03	48867	38.60	39.90	1.30	0.43	2.9	1.51	27	181	<0.5	<5	4.41	3	15	2	241	4.40	<1	0.35	<10	0.78	2119	18	0.01	1	1421	40	0.53	7	3	321	<5	<0.01	<10	<10	41	<10	248	2
8V2278RA/RJ	HL08-03	48868	39.90	40.90	1.00	0.39	1.6	0.61	42	225	<0.5	5	4.90	3	16	3	132	4.46	<1	0.33	<10	0.85	1828	19	0.01	1	1408	35	0.87	7	3	307	<5	<0.01	<10	<10	25	<10	247	2
8V2278RA/RJ	HL08-03	48869	40.90	41.90	1.00	0.37	2.8	0.67	43	115	<0.5	7	3.74	3	15	3	230	4.54	<1	0.35	<10	0.76	1808	31	0.01	<1	1412	31	0.87	5	3	150	<5	<0.01	<10	<10	31	<10	226	2
8V2278RA/RJ	HL08-03	48870	41.90	42.90	1.00	0.17	1.0	0.39	59	129	<0.5	<5	3.23	3	11	20	116	3.80	<1	0.27	<10	0.62	1386	20	0.02	<1	1139	14	1.01	11	3	173	<5	<0.01	<10	<10	20	<10	191	2
8V2278RA/RJ	HL08-03	48871	42.90	43.90	1.00	0.51	2.5	0.77	40	239	<0.5	<5	4.32	3	12	9	214	4.15	<1	0.24	<10	0.92	1874	70	0.02	<1	1112	17	0.79	7	4	194	<5	<0.01	<10	<10	32	<10	159	2
8V2278RA/RJ	HL08-03	48872	43.90	44.90	1.00	0.21	2.0	0.97	26	138	0.5	<5	2.10	3	17	7	164	5.08	<1	0.35	<10	0.99	1715	7	0.01	1	1451													

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V2278RA/RJ	HL08-03	48911	98.40	100.40	2.00	0.13	2.4	1.69	129	67	<0.5	7	2.85	3	22	7	165	5.22	<1	0.27	<10	0.85	1970	13	0.01	3	1256	15	1.64	9	3	98	<5	0.01	<10	<10	68	<10	120	3
8V2278RA/RJ	HL08-03	48912	100.40	102.40	2.00	0.10	2.8	1.86	93	74	<0.5	11	3.53	3	20	4	173	5.42	<1	0.22	<10	1.00	1901	13	0.01	3	1437	16	1.71	7	5	125	<5	0.01	<10	<10	83	<10	148	3
8V2278RA/RJ	HL08-03	48913	102.40	104.40	2.00	0.08	2.5	2.01	80	73	<0.5	9	3.69	3	20	4	178	5.53	<1	0.20	<10	1.24	2117	12	0.01	3	1466	14	1.48	<5	5	143	<5	0.01	<10	<10	95	<10	147	3
8V2278RA/RJ	HL08-03	48914	104.40	106.40	2.00	0.09	2.9	1.76	60	86	<0.5	7	5.54	3	18	9	179	5.77	<1	0.22	<10	1.06	2244	13	0.01	3	1269	10	1.23	6	5	182	<5	0.01	<10	<10	76	<10	113	3
8V2278RA/RJ	HL08-03	48915	106.40	108.40	2.00	0.16	2.7	2.07	36	79	<0.5	7	4.02	3	21	3	230	4.67	<1	0.18	<10	1.13	1899	9	0.02	3	1434	9	0.91	7	7	160	<5	0.06	<10	<10	114	<10	170	3
8V2278RA/RJ	HL08-03	48916	108.40	110.40	2.00	0.10	2.5	1.21	180	68	<0.5	8	4.00	3	14	15	74	4.43	<1	0.21	<10	0.75	2658	10	0.01	1	1043	20	2.24	11	3	142	<5	0.01	<10	<10	47	<10	126	3
8V2278RA/RJ	HL08-03	48917	110.40	112.40	2.00	0.09	3.1	0.99	121	89	<0.5	7	3.25	3	18	7	139	4.98	<1	0.25	<10	0.80	2628	8	0.01	3	1280	63	2.24	8	3	120	<5	<0.01	<10	<10	49	<10	167	3
8V2278RA/RJ	HL08-03	48918	112.40	114.40	2.00	0.16	3.0	1.17	65	68	<0.5	5	3.13	2	14	19	137	4.21	<1	0.19	<10	0.72	2286	6	0.01	1	1089	18	1.35	9	3	76	<5	<0.01	<10	<10	49	<10	111	2
8V2278RA/RJ	HL08-03	48919	114.40	116.40	2.00	0.15	4.9	1.44	54	110	<0.5	8	3.16	2	14	13	189	4.47	<1	0.18	<10	0.84	2640	7	0.01	2	1116	17	1.20	11	4	120	<5	<0.01	<10	<10	64	<10	147	2
8V2278RA/RJ	HL08-03	48920	116.40	117.40	1.00	0.15	6.3	0.79	84	86	<0.5	5	3.73	3	13	23	265	4.42	<1	0.21	<10	0.77	3107	6	0.01	2	1127	27	2.10	11	3	145	<5	<0.01	<10	<10	35	<10	176	2
8V2297RA/RJ	HL08-03	48921	117.40	118.40	1.00	0.35	3.0	0.33	150	73	<0.5	<5	5.35	2	13	20	120	4.62	<1	0.26	<10	0.67	2855	8	0.01	2	954	42	2.38	5	2	250	5	<0.01	<10	<10	20	<10	117	3
8V2297RA/RJ	HL08-03	48922	118.40	119.40	1.00	0.21	2.2	0.96	144	74	<0.5	<5	3.35	2	16	28	84	5.16	<1	0.25	<10	0.81	4036	3	0.01	3	992	44	2.88	<5	2	107	<5	<0.01	<10	<10	43	<10	133	3
8V2297RA/RJ	HL08-03	48923	119.40	120.40	1.00	0.26	2.5	0.73	143	75	<0.5	<5	3.85	3	13	33	34	4.10	<1	0.22	<10	0.65	4235	3	0.01	3	896	306	2.77	<5	2	129	<5	<0.01	<10	<10	31	<10	407	2
8V2297RA/RJ	HL08-03	48924	120.40	121.40	1.00	0.13	2.8	0.55	74	53	<0.5	<5	4.69	5	9	48	105	3.09	<1	0.22	<10	0.43	4070	5	0.01	2	748	245	2.05	<5	1	162	<5	<0.01	<10	<10	17	<10	688	2
8V2297RA/RJ	HL08-03	48925	121.40	122.40	1.00	0.05	0.6	0.74	71	64	<0.5	<5	2.98	2	7	44	14	2.86	<1	0.21	<10	0.58	3407	7	0.01	2	705	46	1.37	<5	2	87	5	<0.01	<10	<10	18	<10	227	2
8V2297RA/RJ	HL08-03	48926	122.40	123.40	1.00	0.03	0.9	0.77	57	65	<0.5	<5	2.67	1	7	58	17	2.99	<1	0.19	<10	0.56	3066	<2	0.01	3	644	79	1.49	<5	2	70	5	<0.01	<10	<10	21	<10	140	2
8V2297RA/RJ	HL08-03	48927	123.40	124.40	1.00	0.06	2.4	0.47	142	68	<0.5	<5	2.01	2	10	53	25	4.07	<1	0.24	<10	0.37	2116	4	0.01	3	736	173	3.37	<5	1	73	<5	<0.01	<10	<10	16	<10	256	3
8V2297RA/RJ	HL08-03	48928	124.40	125.40	1.00	0.10	2.8	0.26	135	60	<0.5	<5	2.17	2	9	52	38	3.59	<1	0.22	<10	0.22	1764	<2	0.01	4	708	138	3.26	<5	1	69	<5	<0.01	<10	<10	8	<10	267	2
8V2297RA/RJ	HL08-03	48929	125.40	126.40	1.00	0.57	1.3	0.26	103	47	<0.5	<5	2.70	1	5	63	<1	1.98	<1	0.18	<10	0.12	1688	3	<0.01	2	377	100	1.66	<5	1	75	<5	<0.01	<10	<10	6	<10	115	2
8V2297RA/RJ	HL08-03	48930	126.40	127.40	1.00	0.16	1.0	0.16	102	54	<0.5	<5	6.09	1	4	87	28	1.93	<1	0.14	<10	0.24	2208	2	<0.01	3	271	118	1.33	<5	1	315	<5	<0.01	<10	<10	4	<10	162	1
8V2297RA/RJ	HL08-03	48931	127.40	128.40	1.00	5.36	1.3	0.44	100	67	<0.5	<5	3.24	2	8	60	39	3.33	<1	0.20	<10	0.43	2720	2	0.01	3	597	35	2.03	<5	1	160	<5	<0.01	<10	<10	15	<10	207	2
8V2297RA/RJ	HL08-03	48932	128.40	129.40	1.00	0.15	1.7	1.06	288	70	<0.5	<5	2.47	2	10	48	126	3.72	<1	0.18	<10	0.63	2632	8	0.01	3	707	69	1.50	<5	2	81	<5	<0.01	<10	<10	39	<10	237	2
8V2297RA/RJ	HL08-03	48933	129.40	130.40	1.00	0.25	4.9	0.61	501	69	<0.5	<5	5.08	3	8	47	36	3.01	<1	0.16	<10	0.34	3416	4	0.01	3	594	478	1.98	6	1	159	<5	<0.01	<10	<10	21	<10	523	2
8V2297RA/RJ	HL08-03	48934	130.40	131.40	1.00	0.16	2.9	0.76	444	64	<0.5	<5	4.29	4	8	62	43	3.15	<1	0.19	<10	0.43	3761	2	0.01	4	557	683	1.88	<5	1	135	<5	<0.01	<10	<10	21	<10	806	2
8V2297RA/RJ	HL08-03	48935	Blank	Blank	0.01	<0.2	0.94	<5	237	0.6	<5	0.44	<1	7	98	<1	2.00	<1	0.52	<10	0.62	571	<2	0.06	5	770	3	0.01	<5	2	51	<5	0.12	<10	<10	39	<10	53	2	
8V2297RA/RJ	HL08-03	48936	Std	PM1110	0.75	165.0	0.66	200	149	<0.5	<5	4.35	2	17	20	4017	3.03	4	0.16	<10	0.19	519	77	0.03	34	791	215	1.29	262	1	177	7	0.05	<10	<10	21	25	239	8	
8V2297RA/RJ	HL08-03	48937	131.40	132.40	1.00	0.08	1.7	1.18	37	57	<0.5	<5	3.57	2	9	45	57	3.34	<1	0.22	<10	0.66	4044	3	0.01	2	721	171	1.01	<5	2	118	<5	<0.01	<10	<10	35	<10	302	2
8V2297RA/RJ	HL08-03	48938	132.40	133.40	1.00	0.07	1.0	1.61	34	63	<0.5	<5	2.77	2	12	49	38	4.40	<1	0.18	<10	1.00	3070	5	0.01	3	730	20	1.00	<5	3	90	<5	0.02	<10	<10	60	<10	205	3
8V2297RA/RJ	HL08-03	48939	133.40	134.40	1.00	0.07	0.2	1.47	16	55	<0.5	<5	3.79	1	10	34	18	3.84	<1	0.16	<10	0.85	3070	2	0.01	3	700	17	0.54	<5	3	167	<5	<0.01	<10	<10	47	<10	147	2
8V2297RA/RJ	HL08-03	48940	134.40	135.40	1.00	0.07	<0.2	1.49	19	80	<0.5	<5	2.59	2	10	43	31	4.06	<1	0.16	<10	0.87	2634	3	0.01	3	810	5	0.49	<5	3	153	<5	<0.01	<10	<10	46	<10	196	2
8V2297RA/RJ	HL08-03	48941	135.40	136.40	1.00	0.06	3.7	1.43	45	58	<0.5	<5	4.98	2	12	24	59	4.18	<1	0.20	<10	0.81	4441	2	0.01	3	829	116	1.20	<5	3	143	<5	<0.01	<10	<10	55	<10	209	2
8V2297RA/RJ	HL08-03	48942	136.40	137.40	1.00	0.05	2.8	1.33	35	54	<0.5	<5	6.27	3	10	35	116	3.61	<1	0.19	<10	0.71	7458	<2	0.01	3	782	250	1.00	<5	3	168	<5	0.01	<10	<10	41	<10	469	2
8V2297RA/RJ	HL08-03	48943	137.40	138.40	1.00	0.05	2.0	1.52	39	55	<0.5	<5	2.95	2	12	33	88	4.17	<1	0.21	<10	0.90	5058	3	0.01	3	884	68	1.16	<5	3	77	<5	0.02	<10	<10	57	<10	238	3
8V2297RA/RJ	HL08-03	48944	138.40	139.40	1.00	0.06	2.1	1.40	34	50	<0.5	<5	3.68	2	11	43	79	4.03	<1	0.20	<10	0.79	3957	2	0.01	3	831	108	1.											

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Int (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																										
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V2297RA/RJ	HL08-03	48983	192.00	193.00	1.00	0.20	3.3	1.34	33	35	<0.5	7	5.86	132	14	26	177	4.15	<1	0.08	<10	0.96	2100	14	0.01	3	591	130	2.12	11	5	56	<5	0.05	<10	<10	55	<10	14500	3
8V2297RA/RJ	HL08-03	48984	193.00	194.00	1.00	0.36	3.1	1.52	62	27	<0.5	8	5.70	168	15	29	111	5.85	<1	0.05	<10	1.09	2400	14	0.01	2	534	155	3.93	9	5	60	<5	0.04	<10	<10	61	<10	18400	3
8V2297RA/RJ	HL08-03	48985	194.00	195.00	1.00	0.08	4.4	1.18	44	24	<0.5	7	10.21	69	11	62	120	4.02	<1	0.04	<10	0.85	3278	40	0.01	7	478	415	1.89	6	7	123	<5	0.03	<10	<10	60	<10	7151	2
8V2297RA/RJ	HL08-03	48986	195.00	196.00	1.00	0.17	7.7	1.20	65	25	<0.5	12	8.10	110	18	122	253	4.05	<1	0.05	<10	0.81	2895	173	<0.01	14	773	1147	2.09	8	8	105	<5	0.03	<10	<10	73	<10	11900	3
8V2297RA/RJ	HL08-03	48987	196.00	197.00	1.00	0.07	6.1	0.87	154	24	<0.5	<5	6.34	69	12	107	260	3.00	<1	0.05	<10	0.51	2085	26	<0.01	12	734	724	1.24	13	7	83	<5	0.03	<10	<10	63	<10	7633	2
8V2297RA/RJ	HL08-03	48988	197.00	198.00	1.00	0.11	4.5	1.88	40	22	<0.5	10	9.12	57	16	158	196	5.29	<1	0.03	<10	1.41	3093	25	<0.01	17	892	349	1.58	8	11	153	<5	0.04	<10	<10	114	<10	6197	4
8V2297RA/RJ	HL08-03	48989	Blank	Blank		<0.01	0.2	0.83	<5	198	<0.5	<5	0.74	3	6	69	11	1.87	<1	0.39	<10	0.54	579	<2	<0.04	4	712	32	0.04	<5	2	32	7	0.12	<10	<10	35	<10	339	2
8V2297RA/RJ	HL08-03	48990	Std	PM 197		0.42	0.4	0.90	6929	18	<0.5	19	5.47	2	166	10	71	3.53	<1	0.04	<10	0.22	625	13	0.06	29	1229	14	1.16	6	1	77	<5	0.04	<10	<10	31	<10	98	9
8V2297RA/RJ	HL08-03	48991	198.00	200.00	2.00	0.08	3.2	1.82	724	39	<0.5	8	8.68	10	22	183	221	4.86	<1	0.08	<10	1.31	3124	40	0.01	25	1243	72	1.02	16	12	135	<5	0.04	<10	<10	124	<10	914	3
8V2297RA/RJ	HL08-03	48992	200.00	202.00	2.00	0.25	3.2	1.80	50	41	<0.5	<5	11.51	7	25	242	345	5.12	<1	0.08	<10	1.04	3365	29	0.01	30	1508	26	0.70	5	20	201	<5	0.07	<10	<10	175	<10	542	4
8V2297RA/RJ	HL08-03	48993	202.00	204.00	2.00	0.57	4.2	1.90	39	40	0.5	<5	6.49	4	25	181	551	5.09	<1	0.09	<10	1.22	2380	70	<0.01	47	1354	16	0.56	9	15	<1	<5	0.08	<10	<10	144	<10	239	5
8V2297RA/RJ	HL08-03	48994	204.00	206.00	2.00	0.42	6.0	2.49	29	80	<0.5	<5	6.28	8	25	204	453	6.52	<1	0.07	<10	1.96	2422	67	<0.01	33	1091	311	0.59	11	16	<1	<5	0.08	<10	<10	162	<10	685	5
8V2297RA/RJ	HL08-03	48995	206.00	208.00	2.00	0.38	5.0	2.06	47	41	<0.5	<5	8.62	4	26	234	441	5.26	<1	0.07	<10	1.50	3015	45	<0.01	33	1356	16	0.60	12	22	<1	<5	0.08	<10	<10	182	<10	248	4
8V2297RA/RJ	HL08-03	48996	208.00	210.00	2.00	0.14	5.7	2.28	117	37	<0.5	<5	6.88	12	25	215	422	5.86	<1	0.08	<10	1.79	3224	39	<0.01	29	1242	190	1.48	13	17	<1	<5	0.04	<10	<10	158	<10	1091	4
8V2297RA/RJ	HL08-03	48997	210.00	211.00	1.00	0.07	3.2	1.91	68	53	<0.5	<5	7.14	4	27	199	301	5.27	<1	0.13	<10	1.18	3305	21	<0.01	33	1309	81	1.04	12	16	<1	<5	0.07	<10	<10	139	<10	296	3
8V2297RA/RJ	HL08-03	48998	211.00	212.00	1.00	0.10	5.4	1.78	97	39	<0.5	<5	8.85	42	18	85	276	4.76	<1	0.07	<10	1.25	3294	29	<0.01	13	875	106	1.21	8	12	<1	<5	0.06	<10	<10	118	<10	3864	3
8V2297RA/RJ	HL08-03	48999	212.00	213.00	1.00	0.05	5.7	2.45	34	61	<0.5	<5	4.53	56	20	86	368	5.34	<1	0.09	<10	1.98	2994	17	<0.01	15	1182	113	0.75	6	14	<1	<5	0.10	<10	<10	173	<10	5343	3
8V2297RA/RJ	HL08-03	49000	213.00	214.00	1.00	0.08	1.4	2.45	54	46	<0.5	<5	5.37	11	19	111	105	5.52	<1	0.09	<10	2.02	3057	30	<0.01	17	1032	90	1.04	8	14	<1	<5	0.08	<10	<10	149	<10	1032	3
8V2297RA/RJ	HL08-03	83501	214.00	215.00	1.00	0.07	2.8	2.81	88	73	<0.5	<5	4.63	16	25	69	293	6.41	<1	0.12	<10	2.21	2684	3	0.02	14	1273	1072	1.48	8	13	<1	<5	0.11	<10	<10	176	<10	1612	4
8V2297RA/RJ	HL08-03	83502	215.00	216.00	1.00	0.03	2.1	2.25	58	85	<0.5	<5	3.52	19	27	64	234	5.38	<1	0.12	<10	1.64	1890	3	0.04	15	1465	615	1.37	6	11	<1	<5	0.13	<10	<10	161	<10	1935	4
8V2297RA/RJ	HL08-03	83503	216.00	217.00	1.00	0.06	4.8	1.86	139	73	<0.5	<5	2.11	84	27	23	431	6.78	<1	0.10	<10	1.41	1535	<2	<0.01	10	1356	2769	4.03	7	7	<1	<5	0.14	<10	<10	122	<10	8452	5
8V2297RA/RJ	HL08-03	83504	217.00	218.00	1.00	0.03	0.8	1.11	39	65	<0.5	<5	1.89	4	20	26	69	3.47	<1	0.10	<10	0.73	1047	3	<0.01	9	1262	87	1.05	6	4	<1	<5	0.15	<10	<10	70	<10	381	4
8V2297RA/RJ	HL08-03	83505	218.00	219.30	1.30	0.07	2.1	1.74	130	48	<0.5	<5	4.53	9	28	39	142	5.70	<1	0.07	<10	1.21	1917	6	<0.01	10	1052	213	1.72	7	9	<1	<5	0.12	<10	<10	116	<10	699	5
8V2297RA/RJ	HL08-03	83506	219.30	220.00	0.70	0.01	0.7	1.16	181	34	<0.5	<5	1.92	2	10	45	37	2.32	<1	0.13	<10	0.85	563	<2	0.01	5	665	118	0.16	5	3	<1	<5	0.09	<10	<10	37	<10	157	7
HL08-04 - Zone: 49er, Pad 13: 435119E, 6223470N, Elev: 1203m, Az: 190, Dip: -45, EOH: 212.50m																																								
8V2297RA/RJ	HL08-04	83507	1.52	4.00	2.48	0.22	5.0	0.48	504	101	<0.5	<5	1.20	3	10	23	34	3.38	<1	0.25	<10	0.15	449	4	<0.01	3	860	109	2.72	12	1	<1	5	<0.01	<10	<10	13	<10	292	2
8V2297RA/RJ	HL08-04	83508	4.00	5.00	1.00	1.90	6.8	0.25	234	86	<0.5	<5	0.56	6	8	60	26	2.92	<1	0.20	<10	0.03	180	4	<0.01	3	654	195	2.94	10	1	<1	9	<0.01	<10	<10	5	<10	667	2
8V2297RA/RJ	HL08-04	83509	5.00	6.00	1.00	5.12	9.9	0.30	372	51	<0.5	<5	0.22	9	12	28	64	4.22	<1	0.25	<10	0.05	97	5	<0.01	4	1021	358	4.78	14	1	<1	12	<0.01	<10	<10	7	<10	1041	3
8V2297RA/RJ	HL08-04	83510	6.00	7.00	1.00	1.48	7.0	0.32	328	52	<0.5	<5	0.26	6	13	46	145	4.43	<1	0.27	<10	0.07	160	21	<0.01	3	1050	180	4.63	13	1	<1	11	<0.01	<10	<10	8	<10	729	3
8V2297RA/RJ	HL08-04	83511	7.00	8.70	1.70	0.14	11.5	1.19	64	139	<0.5	<5	0.31	3	12	15	44	3.95	<1	0.34	<10	0.61	924	7	<0.01	3	1142	54	1.90	8	2	<1	13	<0.01	<10	<10	29	<10	370	2
8V2297RA/RJ	HL08-04	83512	8.70	9.70	1.00	0.20	12.0	0.89	112	85	<0.5	<5	0.30	31	13	34	166	4.52	<1	0.30																				

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Int (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																										
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V2349A/RJ	HL08-04	83554	70.00	71.00	1.00	0.08	1.0	1.57	22	107	<0.5	<5	3.71	1	12	36	134	4.20	<1	0.19	<10	0.85	1715	5	0.02	3	956	5	0.45	<5	3	82	13	0.06	<10	<10	56	<10	122	4
8V2349A/RJ	HL08-04	83555	71.00	73.00	2.00	0.05	0.5	1.32	8	113	<0.5	<5	2.12	1	10	35	146	3.50	<1	0.14	<10	0.82	1158	4	0.03	3	911	6	0.27	<5	2	68	5	0.05	<10	<20	48	<10	93	3
8V2349A/RJ	HL08-04	83556	73.00	75.00	2.00	0.10	0.9	1.07	44	141	<0.5	<5	4.17	1	9	54	97	3.67	<1	0.25	<10	0.61	1463	7	0.02	3	777	7	0.79	<5	2	190	<5	<0.01	<10	27	34	<10	72	2
8V2349A/RJ	HL08-04	83557	75.00	76.00	1.00	0.05	0.5	1.44	7	116	<0.5	<5	2.47	1	12	35	138	3.83	<1	0.10	<10	0.92	1224	8	0.03	3	820	6	0.21	<5	3	78	<5	0.08	<10	19	59	<10	102	4
8V2349A/RJ	HL08-04	83558	76.00	78.00	2.00	0.06	0.6	1.47	12	154	<0.5	<5	2.95	1	10	41	84	3.76	<1	0.18	<10	0.87	1298	6	0.02	3	916	3	0.42	<5	2	109	<5	0.02	<10	21	52	<10	87	2
8V2349A/RJ	HL08-04	83559	78.00	79.60	1.60	0.25	0.3	1.28	<5	232	<0.5	<5	3.49	1	8	28	95	3.27	<1	0.27	<10	0.76	1228	9	0.03	2	913	4	0.27	<5	2	217	5	<0.01	<10	22	36	<10	72	2
8V2349A/RJ	HL08-04	83560	79.60	80.90	1.30	0.05	1.0	0.44	41	286	<0.5	<5	5.02	6	9	38	17	3.46	<1	0.33	<10	0.74	1703	3	0.01	2	914	249	0.68	<5	3	566	<5	<0.01	<10	27	11	<10	454	2
8V2349A/RJ	HL08-04	83561	80.90	81.90	1.00	0.07	1.0	1.28	45	259	<0.5	<5	3.52	1	11	28	76	4.22	<1	0.27	<10	0.81	1629	5	0.02	3	956	8	0.85	<5	3	160	<5	<0.01	<10	20	42	<10	92	3
8V2349A/RJ	HL08-04	83562	81.90	83.90	2.00	0.12	0.8	1.32	28	135	<0.5	<5	3.30	1	10	39	83	3.84	<1	0.28	<10	0.73	1523	5	0.02	3	906	8	0.59	<5	2	154	<5	<0.01	<10	21	37	<10	85	2
8V2349A/RJ	HL08-04	83563	83.90	85.90	2.00	0.38	0.8	1.61	10	204	<0.5	<5	3.90	2	11	29	134	4.05	<1	0.23	<10	0.85	1589	9	0.02	3	894	4	0.35	<5	3	119	<5	0.02	<10	25	50	<10	109	3
8V2349A/RJ	HL08-04	83564	85.90	87.90	2.00	0.13	1.2	1.61	28	111	<0.5	<5	3.87	2	12	27	208	4.41	<1	0.29	<10	0.85	1657	6	0.02	3	1012	24	0.57	<5	3	128	5	<0.01	<10	24	48	<10	129	3
8V2349A/RJ	HL08-04	83565	87.90	89.90	2.00	0.15	0.7	1.48	8	111	<0.5	<5	3.54	1	10	19	112	3.63	<1	0.28	<10	0.79	1388	4	0.02	3	979	7	0.25	<5	2	113	6	<0.01	<10	15	46	<10	105	2
8V2349A/RJ	HL08-04	83566	89.90	91.10	1.20	0.18	1.3	1.39	73	69	<0.5	<5	3.26	1	11	30	111	3.80	<1	0.22	<10	0.72	1532	5	0.01	3	903	10	0.64	<5	2	50	5	<0.01	<10	26	44	<10	100	2
8V2349A/RJ	HL08-04	83567	91.10	93.90	2.80	0.61	1.4	1.27	44	87	<0.5	<5	6.13	1	11	20	143	3.74	<1	0.24	<10	0.56	2313	5	0.01	3	777	15	0.46	<5	2	158	5	<0.01	<10	29	43	<10	109	2
8V2349A/RJ	HL08-04	83568	93.90	95.90	2.00	0.16	1.9	1.42	35	89	<0.5	<5	3.39	2	12	30	229	4.06	<1	0.29	<10	0.58	1485	6	0.01	4	904	7	0.60	<5	2	160	5	<0.01	<10	21	48	<10	125	2
8V2349A/RJ	HL08-04	83569	95.90	97.90	2.00	0.22	1.0	1.46	10	83	<0.5	<5	3.34	2	10	22	190	3.76	<1	0.24	<10	0.70	1336	10	0.02	4	910	6	0.26	<5	3	104	6	<0.01	<10	19	47	<10	128	2
8V2349A/RJ	HL08-04	83570	97.90	99.90	2.00	0.20	3.4	1.60	15	92	<0.5	<5	3.72	2	11	29	2108	3.99	<1	0.28	<10	0.83	1427	17	0.02	4	1126	10	0.29	<5	4	119	<5	0.01	<10	19	54	<10	119	3
8V2349A/RJ	HL08-04	83571	99.90	101.90	2.00	0.20	1.3	1.58	44	68	<0.5	<5	3.39	2	12	24	282	4.23	<1	0.25	<10	0.86	1547	8	0.01	4	926	18	0.77	<5	3	80	5	0.01	<10	22	56	<10	134	3
8V2349A/RJ	HL08-04	83572	101.90	103.50	1.60	0.25	1.9	1.52	19	68	<0.5	<5	3.22	2	12	31	296	3.94	<1	0.24	<10	0.76	1552	9	0.02	5	970	18	0.32	<5	3	83	<5	0.01	<10	23	57	<10	172	2
8V2349A/RJ	HL08-04	83573	103.50	104.50	1.00	0.20	3.7	0.75	85	72	<0.5	<5	4.84	5	9	33	159	3.18	<1	0.28	<10	0.51	2251	6	0.01	4	866	724	1.21	<5	3	197	5	<0.01	<10	25	17	<10	440	2
8V2349A/RJ	HL08-04	83574	104.50	106.50	2.00	0.08	2.0	1.54	66	117	<0.5	<5	3.89	2	15	28	174	4.72	<1	0.26	<10	0.76	1954	5	0.01	5	982	13	0.94	<5	4	122	6	<0.01	<10	26	56	<10	116	3
8V2349A/RJ	HL08-04	83575	106.50	107.80	1.30	0.16	1.4	1.39	131	62	<0.5	<5	3.44	2	14	24	140	4.47	<1	0.21	<10	0.69	1767	6	0.01	5	950	23	1.27	<5	3	80	6	<0.01	<10	31	60	<10	125	3
8V2349A/RJ	HL08-04	83576	107.80	109.80	2.00	0.18	1.1	1.53	30	64	<0.5	<5	3.16	2	12	29	174	4.40	<1	0.19	<10	0.71	1495	10	0.02	4	854	7	0.43	<5	4	93	7	<0.01	<10	23	65	<10	128	3
8V2349A/RJ	HL08-04	83577	109.80	111.80	2.00	0.44	1.8	1.09	92	71	<0.5	<5	3.51	6	12	29	170	4.04	<1	0.21	<10	0.63	1777	12	0.02	3	974	96	1.34	<5	4	157	5	<0.01	<10	28	46	<10	589	2
8V2349A/RJ	HL08-04	83578	111.80	112.80	1.00	0.09	3.8	0.99	116	70	<0.5	<5	3.97	35	11	59	118	3.77	<1	0.16	<10	0.60	2283	5	0.01	3	806	448	1.95	5	3	92	5	<0.01	<10	30	47	<10	3011	2
8V2349A/RJ	HL08-04	83579	112.80	113.80	1.00	0.09	1.9	1.04	179	66	<0.5	<5	2.75	3	11	92	30	4.60	<1	0.23	<10	0.72	2356	4	0.01	5	924	331	2.96	8	3	74	<5	<0.01	<10	31	44	<10	321	3
8V2349A/RJ	HL08-04	83580	113.80	114.80	1.00	0.04	0.6	1.15	67	135	<0.5	<5	3.25	1	7	50	26	3.38	<1	0.25	<10	0.73	2067	3	0.01	3	840	23	1.18	7	2	95	<5	<0.01	<10	23	31	<10	76	3
8V2349A/RJ	HL08-04	83581	114.80	115.80	1.00	0.07	0.3	1.02	84	144	<0.5	<5	3.87	1	8	83	18	3.65	<1	0.34	<10	0.75	2152	4	0.01	5	911	22	1.21	8	3	138	<5	<0.01	<10	22	24	<10	80	3
8V2349A/RJ	HL08-04	83582	115.80	116.80	1.00	0.04	1.3	0.97	70	105	<0.5	<5	1.87	4	8	47	52	3.75	<1	0.37	<10	0.69	1613	4	0.01	3	948	297	1.32	7	3	72	<5	0.01	<10	25	25	<10	401	3
8V2349A/RJ	HL08-04	83583	116.80	117.80	1.00	0.03	0.8	0.62	81	92	<0.5	<5	3.31	4	8	116	25	3.60	<1	0.34	<10	0.59	1844	4	0.01	5	829	117	1.71	9	3	161	<5	<0.01	<10	29	15	<10	323	3
8V2349A/RJ	HL08-04	83584	117.80	118.80	1.00	0.02	0.2	1.17	30	107	<0.5	<5	5.88	1	5	35	6	3.01	<1	0.26	<10	0.65	2385	<2	0.01	3	786	19	0.60	6	3	115	<5	<0.01	<10	23	43	<10	76	3
8V2349A/RJ	HL08-04	83585	118.80	119.90	1.10	0.08	0.2	1.38	16	108	<0.5	<5	2.50	2	5	82	5	3.34	<1	0.25	<10	0.78	1647	2	0.01	4	839	132	0.35	6	3	62	5	<0.01	<10	22	55	<10	136	4
8V2349A/RJ	HL08-04	83586	119.90	120.90	1.00	0.01	3.8	0.52	317	89	<0.5	<5	2.81	14	7	60	83	4.13	<1	0.20	<10	0.52	1801	10	0.01	4	609	1042	2.70	9	2	147	<5	<0.01	<10	28	22	<10	1663	3
8V2349A/RJ	HL08-04	83587	120.90	121.90	1.00	0.18	7.0	0.67	241	85	<0.5	<5	8.12	32	7	72	231	4.22	<1	0.14	<10	0.55	3707	7	0.01	4	691	3048	3.14	13	2	203	<5	<0.01	<10	43	35	<10	3817	

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn: 2500-5000				5000-10000				>10000																		
						Au g/t	Ag g/t	Al %	As ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm	
8V2349A/RJ	HL08-04	83626	188.30	189.30	1.00	0.24	2.8	1.30	19	69	<0.5	<5	8.20	42	15	137	172	3.40	<1	0.09	<10	1.02	2562	21	0.02	18	1200	1611	0.73	7	11	130	<5	0.07	<10	25	103	<10	4930	6
8V2349A/RJ	HL08-04	83627	189.30	191.50	2.20	0.61	2.5	2.09	26	34	<0.5	<5	10.83	3	21	197	333	4.77	<1	0.05	<10	1.89	3732	21	0.01	29	1307	44	0.32	9	12	145	<5	0.08	<10	27	146	<10	289	4
8V2349A/RJ	HL08-04	83628	191.50	192.50	1.00	0.30	1.5	1.14	11	72	<0.5	<5	3.90	2	13	118	221	2.78	<1	0.12	<10	1.22	1187	28	0.03	18	1320	46	0.17	5	6	91	<5	0.08	<10	<10	71	<10	150	6
8V2349A/RJ	HL08-04	83629	200.57	201.50	0.93	0.26	4.0	2.11	112	67	0.5	8	8.03	15	25	219	261	6.13	<1	0.05	<10	1.49	3725	122	0.01	29	1260	597	1.55	11	17	139	<5	0.02	<10	34	164	<10	1601	5
8V2349A/RJ	HL08-04	83630	201.50	202.50	1.00	0.18	2.8	1.20	205	67	<0.5	5	5.19	12	20	211	171	3.99	<1	0.11	<10	0.85	2143	92	0.01	30	1471	105	1.28	10	13	84	<5	0.04	<10	13	145	<10	1106	5
8V2349A/RJ	HL08-04	83631	202.50	203.50	1.00	0.33	4.0	0.75	4718	68	<0.5	8	2.78	8	27	218	91	4.56	<1	0.10	<10	0.41	1468	103	0.01	35	1316	138	2.78	74	11	32	<5	0.01	<10	22	139	<10	926	3
8V2349A/RJ	HL08-04	83632	203.50	204.50	1.00	0.27	5.2	1.10	235	165	<0.5	<5	2.82	4	19	142	444	2.74	<1	0.10	<10	1.02	1158	147	0.02	24	1501	49	0.33	9	5	67	<5	0.09	<10	14	86	<10	298	4
8V2349A/RJ	HL08-04	83633	204.50	205.50	1.00	0.40	4.2	1.00	66	65	<0.5	<5	3.47	3	17	140	169	3.25	<1	0.08	<10	0.73	1263	134	0.02	20	1475	89	0.88	6	5	79	<5	0.07	<10	13	75	<10	358	6
8V2349A/RJ	HL08-04	83634	205.50	206.50	1.00	0.14	25.2	1.17	287	90	<0.5	<5	3.94	4	20	180	309	4.10	<1	0.10	<10	0.80	1813	77	0.02	28	1579	162	1.30	14	9	71	<5	0.08	<10	18	121	<10	606	6
8V2349A/RJ	HL08-04	83635	206.50	207.50	1.00	0.86	175.8	1.21	1824	59	<0.5	9	5.24	46	27	195	693	6.40	<1	0.07	<10	0.76	2562	47	0.01	35	1361	9078	4.43	50	9	82	<5	0.05	<10	35	124	<10	8656	6
8V2349A/RJ	HL08-04	83636	207.50	208.50	1.00	1.02	177.4	1.04	>10000	77	<0.5	8	3.10	28	27	236	441	6.14	<1	0.10	<10	0.62	1542	59	0.01	34	1597	3795	3.66	331	10	43	<5	0.04	<10	30	144	<10	5825	5
8V2349A/RJ	HL08-04	83637	208.50	209.50	1.00	0.50	24.9	0.93	6130	40	<0.5	8	6.17	15	23	178	213	5.49	<1	0.07	<10	0.51	1987	97	0.01	26	1092	688	3.34	98	9	59	<5	0.03	<10	28	111	<10	3030	4
8V2349A/RJ	HL08-04	83638	209.50	210.50	1.00	0.46	15.3	1.46	278	59	<0.5	<5	4.23	4	22	146	160	4.49	<1	0.06	<10	0.95	1857	93	0.02	22	1633	75	0.79	11	7	95	<5	0.07	<10	23	93	<10	556	8
8V2349A/RJ	HL08-04	83639	210.50	211.50	1.00	0.65	5.9	1.03	62	44	<0.5	<5	5.97	2	15	83	573	2.64	<1	0.09	<10	0.69	1485	121	0.01	12	1284	15	0.17	5	5	100	<5	0.06	<10	16	62	<10	245	6
8V2349A/RJ	HL08-04	83640	211.50	212.50	1.00	0.34	4.5	0.60	81	80	<0.5	<5	>15.00	2	10	65	374	2.22	<1	0.06	<10	0.32	5958	65	0.02	9	536	30	0.33	<5	5	223	<5	0.04	<10	36	45	<10	140	3
HL08-05 - Zone: 49er, Pad 13: 435119E, 6223470N, Elev: 1203m, Az: 245, Dip: -45, OEH: 93.60m																																								
8V2349A/RJ	HL08-05	83641	1.52	3.50	1.98	3.56	20.3	0.27	546	51	<0.5	10	0.41	6	7	58	101	4.36	<1	0.20	<10	0.06	234	5	0.01	3	681	315	3.41	20	1	12	5	<0.01	<10	<10	8	<10	776	3
8V2349A/RJ	HL08-05	83642	3.50	5.50	2.00	0.18	7.6	1.01	163	105	<0.5	7	0.39	2	12	26	111	3.83	<1	0.30	<10	0.43	730	16	0.01	4	1226	49	2.10	7	1	11	5	<0.01	<10	<10	21	<10	212	3
8V2349A/RJ	HL08-05	83643	5.50	6.50	1.00	0.28	4.2	0.68	247	82	<0.5	6	0.37	2	12	33	107	3.84	<1	0.28	<10	0.26	425	12	0.01	4	1158	87	3.04	7	1	14	5	<0.01	<10	11	15	<10	199	3
8V2349A/RJ	HL08-05	83644	6.50	7.50	1.00	0.65	6.9	0.73	324	71	<0.5	8	0.34	3	11	35	195	4.09	<1	0.28	<10	0.28	498	18	0.01	4	1176	124	3.30	8	1	12	5	<0.01	<10	10	12	<10	390	3
8V2349A/RJ	HL08-05	83645	7.50	9.50	2.00	0.28	3.0	1.03	102	146	<0.5	<5	0.38	2	10	28	74	3.34	<1	0.30	<10	0.44	838	6	0.01	3	1147	68	1.55	5	1	20	<5	<0.01	<10	<10	26	<10	215	3
8V2349A/RJ	HL08-05	83646	9.50	11.50	2.00	0.08	4.5	1.19	79	149	<0.5	6	0.32	1	11	24	121	3.30	<1	0.30	<10	0.53	912	15	0.01	4	1185	89	0.96	5	1	14	6	<0.01	<10	<10	29	<10	110	2
8V2349A/RJ	HL08-05	83647	11.50	13.50	2.00	0.21	2.2	1.46	202	138	<0.5	5	0.36	2	12	17	68	4.02	<1	0.28	<10	0.79	1157	5	0.01	3	1235	24	1.05	5	2	15	5	<0.01	<10	<10	37	<10	178	3
8V2349A/RJ	HL08-05	83648	13.50	15.50	2.00	0.14	1.7	1.64	119	142	<0.5	6	0.52	1	11	21	88	4.22	<1	0.28	<10	0.98	1347	4	0.01	3	1174	13	0.82	5	2	27	5	<0.01	<10	12	45	<10	101	3
8V2349A/RJ	HL08-05	83649	15.50	17.50	2.00	0.11	1.7	1.60	162	119	<0.5	<5	0.75	2	10	25	85	4.17	<1	0.24	<10	0.92	1404	5	0.01	3	1116	30	0.82	<5	2	49	5	<0.01	<10	13	45	<10	131	3
8V2349A/RJ	HL08-05	83650	17.50	18.50	1.00	0.14	1.7	1.53	553	128	<0.5	7	0.61	2	11	27	74	4.05	<1	0.27	<10	0.90	1371	7	0.01	4	1184	16	0.86	7	2	26	5	<0.01	<10	15	45	<10	119	3
8V2349A/RJ	HL08-05	83651	18.50	19.20	0.70	0.14	3.0	0.83	184	71	<0.5	<5	1.07	2	12	47	47	4.93	<1	0.32	<10	0.36	814	4	0.01	5	853	32	4.14	5	1	73	<5	<0.01	<10	<10	27	<10	85	3
8V2349A/RJ	HL08-05	83652	19.20	20.20	1.00	0.09	3.0	1.34	125	139	<0.5	<5	0.65	3	12	32	69	4.00	<1	0.40	<10	0.60	919	11	0.01	4	1002	75	2.04	<5	2	29	<5	<0.01	<10	<10	38	<10	242	3
8V2349A/RJ	HL08-05	83653	20.20	21.20	1.00	0.13	2.7	1.10	139	102	<0.5	<5	0.40	2	13	40	101	4.00	<1	0.38	<10	0.42	647	7	0.01	4	1016	42	2.62	<5	2	28	<5	<0.01	<10	<10	26	<10	129	3
8V2349A/RJ	HL08-05	83654	21.20	22.20	1.00	0.08	1.9	1.37	117	122	<0.5	<5	0.58	2	12	66	57	4.33	<1	0.42	<10	0.60	900	4	0.01	5	956	29	2.40	<5	2	40	<5	<0.01	<10	<10	34	<10	126	3
8V2349A/RJ	HL08-05	83655	22.20	23.20	1.00	0.11	3.7	0.85	140	84	<0.5	<5	0.61	6	10	66	127	3.76	<1	0.32	<10	0.36	671	5	0.01	4	807	98	2.71	6	1	49	<5	<0.01	<10					

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V2376RA/RJ	HL08-05	83697	92.00	93.59	1.59	0.11	1.6	1.49	<5	374	<0.5	5	3.03	1	14	25	297	3.65	<1	0.25	<10	0.72	1308	7	0.03	2	1157	5	0.39	<5	4	105	<5	0.05	<10	24	57	<10	103	3
HL08-06 - Zone: Yellowstone, Pad 14: 435045E, 6223625N, Elev: 1212m, Az: 260, Dip: -52, EOH: 121.04m																																								
8V2376RA/RJ	HL08-06	83698	1.24	3.00	1.76	0.02	0.5	2.37	37	159	<0.5	7	3.08	2	12	14	9	5.27	<1	0.25	<10	1.18	1557	<2	0.02	2	1511	8	0.70	<5	3	76	<5	0.03	<10	31	40	<10	97	3
8V2376RA/RJ	HL08-06	83699	3.00	5.00	2.00	0.02	0.5	2.55	49	148	<0.5	7	2.54	2	13	8	9	5.60	<1	0.22	<10	1.30	1622	<2	0.02	2	1678	8	0.55	<5	4	56	<5	0.03	<10	35	48	<10	111	3
8V2376RA/RJ	HL08-06	83700	5.00	7.00	2.00	0.05	1.5	2.11	102	134	<0.5	8	2.43	29	11	8	19	4.94	<1	0.22	<10	1.07	1430	<2	0.02	2	1388	292	1.01	5	60	<5	0.02	<10	27	43	<10	3090	3	
8V2376RA/RJ	HL08-06	83701	7.00	8.50	1.50	0.27	5.7	1.77	665	112	<0.5	7	1.86	29	12	24	38	5.31	1	0.23	<10	0.88	1281	3	0.02	3	1388	837	2.33	13	2	51	<5	0.04	<10	30	35	<10	3228	3
8V2376RA/RJ	HL08-06	83702	8.50	10.00	1.50	0.09	1.5	1.67	311	155	<0.5	7	1.62	3	11	11	30	4.63	<1	0.24	<10	0.83	1247	3	0.02	2	1378	78	1.42	7	2	33	<5	0.03	<10	25	33	<10	256	3
8V2376RA/RJ	HL08-06	83703	10.00	11.20	1.20	0.04	1.1	2.16	134	146	<0.5	6	1.81	3	13	21	24	5.44	<1	0.22	<10	1.14	1653	2	0.03	3	1632	125	1.39	5	3	47	<5	0.03	<10	26	47	<10	245	4
8V2376RA/RJ	HL08-06	83704	11.20	12.20	1.00	0.17	20.8	1.44	386	42	<0.5	11	0.63	28	13	14	431	6.23	1	0.24	<10	0.71	1052	<2	0.02	2	1282	1055	4.29	24	2	22	<5	0.02	<10	29	29	<10	2862	4
8V2376RA/RJ	HL08-06	83705	12.20	13.20	1.00	0.15	6.8	1.59	273	134	<0.5	7	1.20	9	11	21	75	4.82	<1	0.26	<10	0.77	1395	2	0.02	2	1340	387	2.06	9	2	38	<5	0.05	<10	22	31	<10	1051	3
8V2376RA/RJ	HL08-06	83706	13.20	14.20	1.00	0.27	11.7	0.75	271	39	<0.5	12	0.96	75	9	30	413	6.29	3	0.28	<10	0.25	703	<2	0.02	2	936	2091	>5.00	15	1	47	<5	0.01	<10	29	16	<10	8196	4
8V2376RA/RJ	HL08-06	83707	14.20	15.20	1.00	0.23	8.1	0.79	309	39	<0.5	14	2.50	45	11	45	45	7.11	2	0.31	<10	0.24	1161	3	0.02	3	1081	2256	>5.00	11	1	88	<5	0.01	<10	40	18	<10	4988	4
8V2376RA/RJ	HL08-06	83708	15.20	16.20	1.00	0.32	9.7	0.59	333	54	<0.5	9	0.81	37	10	34	121	5.42	1	0.26	<10	0.20	570	<2	0.01	4	743	1111	>5.00	14	1	53	<5	0.01	<10	25	16	<10	4239	3
8V2376RA/RJ	HL08-06	83709	16.20	17.20	1.00	0.36	7.5	0.99	295	84	<0.5	10	1.39	40	12	52	59	4.97	2	0.29	<10	0.41	1048	<2	0.01	4	876	1754	3.95	13	2	74	<5	0.01	<10	23	28	<10	4935	3
8V2376RA/RJ	HL08-06	83710	17.20	18.20	1.00	0.50	6.0	0.85	342	94	<0.5	10	2.04	13	11	35	47	4.17	<1	0.32	<10	0.27	1110	<2	0.01	3	867	583	3.26	9	2	83	<5	0.01	<10	22	20	<10	1592	3
8V2376RA/RJ	HL08-06	83711	18.20	19.20	1.00	0.53	6.6	0.56	448	115	<0.5	6	0.41	9	8	50	35	2.98	<1	0.29	<10	0.11	369	3	0.01	3	912	367	2.44	9	1	17	<5	<0.01	<10	15	10	<10	1043	2
8V2376RA/RJ	HL08-06	83712	19.20	20.20	1.00	0.66	19.0	0.35	3052	57	<0.5	10	0.08	13	7	63	30	4.64	1	0.21	<10	0.08	184	3	0.01	4	573	1196	4.52	53	1	2	<5	<0.01	<10	19	10	<10	1501	3
8V2376RA/RJ	HL08-06	83713	20.20	21.20	1.00	0.75	21.5	0.22	2766	59	<0.5	10	<0.01	4	5	115	24	4.38	<1	0.14	<10	0.05	135	2	0.01	4	316	187	4.13	57	<1	<1	<5	<0.01	<10	15	7	<10	414	3
8V2376RA/RJ	HL08-06	83714	21.20	21.80	0.60	2.22	1008.0	0.14	802	52	<0.5	10	0.02	37	4	113	328	4.99	1	0.10	<10	0.06	137	<2	0.01	5	283	3473	>5.00	152	<1	1	<5	<0.01	<10	<10	7	<10	6096	3
8V2376RA/RJ	HL08-06	83715	21.80	22.40	0.60	3.20	8260.0	<0.01	1820	10	<0.5	29	<0.01	327	2	136	1326	14.26	8	0.04	24	0.01	56	<2	0.01	5	172	3590	>5.00	1026	<1	1	<5	<0.01	<10	37	7	<10	5500	9
8V2376RA/RJ	HL08-06	83716	22.40	23.20	0.80	1.46	891.0	<0.08	1590	18	<0.5	22	<0.01	104	4	144	206	10.61	3	0.10	13	0.03	138	<2	0.01	6	209	5398	>5.00	134	<1	8	<5	<0.01	<10	22	7	<10	16000	7
8V2376RA/RJ	HL08-06	83717	23.20	23.65	0.45	1.25	1103.0	0.42	834	31	<0.5	14	0.05	61	5	150	107	7.61	2	0.19	<10	0.16	508	2	0.01	6	544	3955	>5.00	96	1	6	<5	<0.01	<10	18	15	<10	9467	5
8V2376RA/RJ	HL08-06	83718	23.65	24.43	0.78	2.66	1740.0	<0.01	2090	<10	<0.5	31	<0.01	250	3	174	253	>15.00	6	0.04	11	0.01	220	<2	<0.01	6	137	1070	>5.00	279	<1	4	<5	<0.01	<10	50	8	<10	40500	10
8V2376RA/RJ	HL08-06	83719	24.43	25.00	0.57	0.36	48.7	0.27	637	63	<0.5	7	0.04	6	5	175	28	4.15	1	0.15	11	0.09	253	4	0.01	6	277	405	3.93	28	<1	5	<5	<0.01	<10	10	7	<10	823	3
8V2376RA/RJ	HL08-06	83720	25.00	26.00	1.00	0.35	20.0	0.39	306	73	<0.5	<5	1.06	5	4	138	25	1.82	<1	0.15	<10	0.18	800	2	0.01	4	343	241	1.16	14	1	39	<5	<0.01	<10	12	10	<10	685	2
8V2376RA/RJ	HL08-06	83721	Blank	Blank	<0.01	4.1	1.02	<5	226	<0.5	<5	0.51	1	6	172	1	2.01	<1	0.48	11	0.60	544	2	0.08	8	723	21	0.03	5	2	69	<5	0.15	<10	<10	37	<10	72	3	
8V2376RA/RJ	HL08-06	83722	Std PM 1110		1.77	152.9	0.82	202	190	<0.5	93	5.09	2	15	20	3607	3.42	4	0.17	<10	0.17	606	73	0.03	31	616	195	1.20	243	2	170	<5	0.07	<10	<10	21	21	232	11	
8V2376RA/RJ	HL08-06	83723	26.00	27.00	1.00	0.27	8.7	0.82	236	115	<0.5	<5	0.66	1	6	98	42	2.33	<1	0.19	<10	0.47	1114	2	0.01	4	610	26	0.77	12	1	45	<5	<0.01	<10	33	<10	66	2	
8V2376RA/RJ	HL08-06	83724	27.00	28.00	1.00	0.30	17.0	0.67	253	95	<0.5	<5	0.52	7	8	92	30	3.26	<1	0.16	<10	0.47	960	2	0.01	6	660	193	2.09	14	1	34	<5	<0.01	<10	12	27	<10	910	3
8V2376RA/RJ	HL08-06	83725	28.00	29.00	1.00	0.55	6.2	1.12	222	132	<0.5	5	1.72	6	9	52	31	3.94	<1	0.22	<10	0.67	1808	<2	0.01	4	855	104	1.93	7	2	60	<5	<0.01	<10	19	49	<10	798	3
8V2376RA/RJ	HL08-06	83726	29.00	30.00	1.00	0.43	6.7	1.18	250	130	<0.5	<5	1.86	5	9	64	33	3.43	<1	0.29	<10	0.62	1614	2	0.01	4	892	79	1.36	7	2	88	<5	0.01	<10	10	39	<10	535	3
8V2376RA/RJ																																								

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0					Ag: 5-10 10-50 50-100 >100					Pb/Zn: 2500-5000 5000-10000 >10000																									
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V2415RA/RJ	HL08-07	83766	25.70	27.70	2.00	0.29	4.2	0.79	141	86	<0.5	<5	6.46	2	5	46	26	2.49	<1	0.15	<10	0.47	2408	<2	0.01	2	586	67	1.00	9	2	114	<5	0.01	<10	17	32	<10	212	2
8V2415RA/RJ	HL08-07	83767	27.70	29.70	2.00	0.30	4.2	0.91	320	102	<0.5	<5	0.68	3	8	40	21	3.45	<1	0.19	<10	0.53	1396	3	0.01	2	740	90	1.83	9	2	34	<5	0.02	<10	13	47	<10	283	3
8V2415RA/RJ	HL08-07	83768	29.70	31.00	1.30	0.28	5.1	1.53	231	91	<0.5	5	1.76	2	15	24	112	4.93	<1	0.14	<10	0.97	2550	3	0.01	4	886	49	1.84	7	5	65	<5	0.03	<10	24	113	<10	94	3
8V2415RA/RJ	HL08-07	83769	31.00	33.00	2.00	0.26	2.9	1.87	235	94	<0.5	6	1.97	2	18	11	100	5.53	<1	0.19	<10	1.06	2586	5	0.01	4	1037	34	1.71	5	5	77	<5	0.01	<10	27	116	<10	66	3
8V2415RA/RJ	HL08-07	83770	33.00	35.00	2.00	0.31	3.0	1.53	419	74	<0.5	7	1.78	2	18	13	42	5.55	<1	0.17	<10	0.99	2039	<2	0.01	5	840	34	2.70	5	4	68	<5	0.01	<10	27	113	<10	95	3
8V2415RA/RJ	HL08-07	83771	35.00	37.00	2.00	0.09	2.0	1.61	135	135	<0.5	6	2.96	2	20	13	59	4.55	<1	0.33	<10	0.77	1885	<2	0.01	4	1100	34	1.43	<5	3	70	<5	<0.01	<10	21	57	<10	110	3
8V2415RA/RJ	HL08-07	83772	37.00	39.00	2.00	0.07	1.3	1.37	86	107	<0.5	7	2.45	1	17	6	51	4.09	<1	0.39	<10	0.53	1233	<2	0.01	3	1284	14	1.62	<5	3	56	<5	<0.01	<10	16	46	<10	58	3
8V2415RA/RJ	HL08-07	83773	39.00	41.00	2.00	0.33	1.2	1.04	423	82	<0.5	5	4.61	2	17	10	41	4.51	<1	0.35	<10	0.44	1324	<2	0.01	2	1319	19	3.28	8	3	118	<5	0.01	<10	23	34	<10	78	3
8V2415RA/RJ	HL08-07	83774	41.00	43.00	2.00	0.05	1.2	1.54	101	113	<0.5	5	4.94	2	18	6	46	4.25	<1	0.29	<10	0.76	1566	<2	0.01	3	1246	16	1.68	<5	4	124	<5	0.01	<10	32	51	<10	83	2
8V2415RA/RJ	HL08-07	83775	43.00	45.00	2.00	0.04	0.8	1.27	97	87	<0.5	5	3.82	2	16	13	39	4.48	<1	0.32	<10	0.63	1302	<2	0.01	1	1334	27	2.65	<5	3	104	<5	0.01	<10	17	34	<10	56	3
8V2415RA/RJ	HL08-07	83776	45.00	47.00	2.00	0.02	0.8	1.51	72	87	<0.5	6	4.17	2	18	6	38	4.81	<1	0.33	<10	0.84	1605	<2	0.01	2	1324	34	2.79	<5	3	104	<5	0.01	<10	24	37	<10	59	3
8V2415RA/RJ	HL08-07	83777	47.00	49.00	2.00	0.06	0.9	1.28	135	61	<0.5	7	3.93	3	21	19	43	5.37	<1	0.34	<10	0.70	1499	<2	0.01	3	1368	38	4.07	6	3	103	<5	0.02	<10	25	36	<10	73	4
8V2415RA/RJ	HL08-07	83778	49.00	51.00	2.00	0.18	1.0	0.72	269	65	<0.5	6	3.98	2	14	11	30	3.86	<1	0.30	<10	0.29	1217	2	0.01	2	1146	40	3.31	7	2	103	<5	0.02	<10	18	17	<10	75	3
8V2415RA/RJ	HL08-07	83779	51.00	53.00	2.00	0.03	0.8	1.49	106	91	<0.5	<5	4.90	2	12	10	24	4.46	<1	0.25	<10	0.81	1725	<2	0.01	1	1203	34	1.88	5	2	103	<5	<0.01	<10	23	34	<10	61	3
8V2415RA/RJ	HL08-07	83780	53.00	55.00	2.00	0.03	0.5	1.68	67	98	<0.5	<5	4.40	2	12	7	24	4.33	<1	0.23	<10	0.93	2014	<2	0.02	2	1255	25	1.11	<5	2	108	<5	<0.01	<10	24	53	<10	62	3
8V2415RA/RJ	HL08-07	83780A	55.00	59.00	4.00	0.02	0.5	1.78	71	85	<0.5	<5	3.93	1	12	11	23	4.27	<1	0.19	<10	1.09	2130	<2	0.02	1	1263	23	0.67	<5	3	98	<5	0.01	<10	20	57	<10	73	3
8V2415RA/RJ	HL08-07	83780B	59.00	63.11	4.11	0.17	6.4	1.88	1156	85	<0.5	<5	3.00	47	12	6	67	4.51	<1	0.23	<10	1.11	1880	<2	0.02	2	1264	1016	0.93	8	2	81	<5	0.01	<10	21	55	<10	4004	3
HL08-08 - Zone: Yellowstone, Pad 14: 435049E, 6223623N, Elev: 1212m, Az: 157, Dip: -50, EOH: 142.38m																																								
8V2415RA/RJ	HL08-08	83781	3.50	5.50	2.00	0.01	0.7	2.21	170	130	<0.5	<5	2.12	2	12	13	8	5.01	<1	0.20	<10	1.07	1273	2	0.02	1	1413	13	0.53	5	3	53	<5	0.01	<10	18	40	<10	130	3
8V2415RA/RJ	HL08-08	83782	7.50	8.50	1.00	<0.01	0.5	2.13	26	109	<0.5	<5	4.99	4	10	6	28	4.79	<1	0.19	<10	1.06	1761	2	0.02	1	1444	76	0.65	<5	3	124	<5	0.02	<10	22	42	<10	275	3
8V2415RA/RJ	HL08-08	83783	8.50	9.50	1.00	0.05	1.1	2.36	23	103	<0.5	5	2.64	5	12	8	16	5.13	<1	0.17	<10	1.23	1540	2	0.01	2	1324	193	0.47	5	3	62	5	0.02	<10	29	42	<10	477	3
8V2415RA/RJ	HL08-08	83784	9.50	11.50	2.00	0.04	1.2	2.14	85	109	<0.5	5	2.40	2	12	11	10	5.18	<1	0.19	<10	1.11	1410	<2	0.01	2	1330	25	1.13	5	3	60	5	0.02	<10	26	40	<10	123	3
8V2415RA/RJ	HL08-08	83785	11.50	13.50	2.00	0.02	0.6	2.45	36	99	<0.5	<5	2.82	2	13	6	2	5.47	<1	0.15	<10	1.35	1750	<2	0.02	2	1398	11	0.75	<5	4	72	5	0.05	<10	29	57	<10	130	3
8V2415RA/RJ	HL08-08	83786	13.50	15.00	1.50	0.19	20.1	1.10	309	47	<0.5	7	3.36	28	13	19	538	5.60	<1	0.21	<10	0.51	1397	<2	0.01	2	1128	1765	4.98	17	2	98	<5	0.06	<10	24	22	<10	3257	3
8V2415RA/RJ	HL08-08	83787	15.00	16.50	1.50	0.06	0.8	2.20	89	128	<0.5	5	1.23	2	14	8	5	4.48	<1	0.22	<10	1.17	1434	<2	0.01	2	1469	29	1.46	5	3	37	5	0.07	<10	21	46	<10	126	3
8V2415RA/RJ	HL08-08	83788	16.50	18.00	1.50	0.18	10.5	8.84	277	45	<0.5	5	1.32	15	11	23	388	4.30	<1	0.22	<10	0.34	692	<2	0.01	2	952	768	3.42	12	2	54	6	0.02	<10	24	18	<10	1632	2
8V2415RA/RJ	HL08-08	83789	18.00	19.50	1.50	0.42	16.7	0.33	386	91	<0.5	<5	0.89	12	6	49	92	2.91	<1	0.17	<10	0.08	406	3	0.01	2	423	568	2.53	18	1	17	5	<0.01	13	18	6	<10	1407	2
8V2415RA/RJ	HL08-08	83790	19.50	20.50	1.00	2.13	14.5	0.14	391	42	<0.5	7	0.09	27	5	81	119	3.97	<1	0.12	<10	0.02	71	3	0.01	2	230	876	4.22	18	<1	<1	6	<0.01	<10	22	3	<10	3297	2
8V2415RA/RJ	HL08-08	83791	20.50	21.50	1.00	0.27	4.4	0.43	212	74	<0.5	6	0.46	13	9	54	52	3.54	<1	0.19	<10	0.17	399	2	0.01	3	576	437	3.15	11	1	9	6	<0.01	10	21	9	<10	1630	2
8V2415RA/RJ	HL08-08	83792	21.50	22.50	1.00	0.38	5.5	0.52	320	69	<0.5	6	0.77	3	9	44	22	3.68	<1	0.25	<10	0.16	449	3	0.01	3	782	104	3.27	16	1	15	6	<0.01	12	20	12	<10	390	2
8V2415RA/RJ	HL08-08	83793	22.50	24.00	1.50	0.32	4.3	0.64	279	91	<0.5	6	0.49	4	10	37	17	3.37	<1	0.27	<10	0.21	460	3	0.01	3	819	238	2.60	13	1	<1	7	<0.01	20	20	15	<10	486	2
8V2415RA/RJ	HL08-08	83794	24.00	26.00	2.00	0.27																																		

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																										
						Au g/t	Ag g/t	Al %	As ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm	
8V3672RA/RJ	HL08-08	122732	93.00	95.00	2.00	0.02	1.8	2.64	16	118	<0.5	<5	3.38	2	27	6	180	6.12	<1	0.27	<10	2.21	2289	<2	0.02	4	1466	50	0.87	<5	7	131	<5	0.09	<10	11	159	<10	131	3
8V3672RA/RJ	HL08-08	122733	95.00	97.00	2.00	0.06	1.1	2.45	41	131	<0.5	5	3.63	2	26	5	91	5.91	<1	0.31	<10	1.97	2315	<2	0.03	4	1435	42	0.93	<5	6	164	<5	0.04	<10	13	136	<10	120	3
8V3672RA/RJ	HL08-08	122734	97.00	99.00	2.00	0.38	3.0	1.68	144	145	<0.5	<5	2.36	5	16	7	177	4.16	<1	0.42	<10	0.86	1445	46	0.01	2	1334	38	0.71	<5	3	76	<5	0.02	<10	<10	50	<10	255	2
8V2415RA/RJ	HL08-08	83813	99.00	101.00	2.00	0.01	0.8	2.33	12	159	<0.5	<5	4.69	2	20	3	75	5.31	<1	0.30	<10	1.47	2094	<2	0.01	4	1208	34	1.16	<5	4	185	<5	0.02	<10	24	74	<10	82	3
8V2415RA/RJ	HL08-08	83814	101.00	103.00	2.00	0.40	1.7	1.42	345	61	<0.5	7	4.40	2	21	11	59	5.49	<1	0.32	<10	0.86	1846	<2	0.01	5	1156	47	3.95	6	178	<5	0.01	<10	26	60	<10	76	3	
8V2415RA/RJ	HL08-08	83815	103.00	105.00	2.00	0.49	2.0	1.39	525	59	<0.5	8	3.40	3	26	25	58	6.74	<1	0.34	<10	0.99	1389	<2	0.01	6	1515	39	>5.00	8	3	126	<5	0.02	<10	27	55	<10	69	4
8V2415RA/RJ	HL08-08	83816	105.00	107.00	2.00	0.36	1.6	1.56	298	69	<0.5	5	4.24	2	23	12	86	5.88	<1	0.32	<10	1.07	1657	<2	0.01	6	1238	38	4.40	7	4	172	<5	0.01	<10	27	57	<10	67	4
8V2415RA/RJ	HL08-08	83817	107.00	109.00	2.00	0.09	1.5	2.86	50	113	<0.5	<5	2.92	2	28	31	101	5.58	<1	0.27	<10	2.16	2152	2	0.01	19	916	44	0.54	<5	7	93	<5	0.01	<10	27	116	<10	107	3
8V2415RA/RJ	HL08-08	83818	109.00	111.00	2.00	0.09	1.9	2.22	63	169	<0.5	<5	3.53	2	23	14	94	5.07	<1	0.38	<10	1.07	2131	13	0.01	7	1166	36	0.80	5	5	101	<5	0.01	<10	22	79	<10	141	3
8V2415RA/RJ	HL08-08	83819	111.00	113.00	2.00	0.26	2.2	1.83	50	122	<0.5	5	3.47	13	14	9	109	4.37	<1	0.32	<10	0.80	2180	36	0.01	2	1267	46	0.71	<5	2	103	<5	0.01	<10	24	40	<10	521	3
8V2415RA/RJ	HL08-08	83820	113.00	115.00	2.00	0.35	2.1	1.70	171	119	<0.5	<5	4.21	15	13	8	95	4.30	<1	0.33	<10	0.75	2399	21	0.01	2	1309	41	1.09	<5	2	139	<5	0.01	<10	22	33	<10	696	3
8V2415RA/RJ	HL08-08	83821	115.00	117.00	2.00	0.53	7.4	1.70	123	140	<0.5	<5	2.76	31	14	10	269	4.45	<1	0.34	<10	0.69	2030	16	0.01	2	1278	110	1.01	<5	2	77	<5	0.04	<10	19	40	<10	1253	3
8V3672RA/RJ	HL08-08	122709	117.00	119.00	2.00	0.31	4.3	1.86	92	200	<0.5	<5	1.98	8	17	10	186	4.26	<1	0.50	<10	0.69	1576	38	0.01	2	1412	30	0.73	<5	2	65	<5	0.01	<10	<10	36	<10	395	2
8V2415RA/RJ	HL08-08	83822	119.00	120.50	1.50	0.44	3.7	1.48	96	161	<0.5	5	1.58	3	11	12	180	3.74	<1	0.33	<10	0.55	1406	34	0.01	1	1329	36	0.60	<5	2	51	<5	<0.01	<10	16	30	<10	288	2
8V3672RA/RJ	HL08-08	122735	120.50	122.50	2.00	0.22	1.7	2.20	30	151	<0.5	<5	4.39	2	20	4	141	5.16	<1	0.45	<10	1.22	2010	14	0.02	1	1463	30	0.63	<5	3	105	<5	0.03	<10	<10	65	<10	288	2
8V3672RA/RJ	HL08-08	122736	122.50	124.50	2.00	0.80	1.0	2.11	68	127	<0.5	<5	3.82	3	19	7	78	4.99	<1	0.39	<10	1.15	1757	170	0.02	1	1385	34	0.23	<5	4	90	<5	0.12	<10	<10	67	<10	260	2
8V3672RA/RJ	HL08-08	122737	124.50	126.00	1.50	0.84	1.2	1.94	20	130	<0.5	<5	3.89	2	18	6	116	4.53	<1	0.41	<10	1.03	1654	61	0.02	1	1400	25	0.37	<5	3	91	<5	0.12	<10	<10	56	<10	216	2
8V3672RA/RJ	HL08-08	122738	126.00	127.00	1.00	0.34	1.6	2.10	24	126	<0.5	<5	4.51	2	21	5	202	4.99	<1	0.38	<10	1.21	2023	9	0.02	1	1346	23	0.43	<5	4	99	<5	0.13	<10	<10	68	<10	298	3
8V2415RA/RJ	HL08-08	83823	127.00	133.00	6.00	0.44	1.9	2.09	40	109	<0.5	<5	5.51	3	16	11	287	5.18	<1	0.33	<10	0.97	1939	56	0.02	1	1339	33	0.73	<5	4	119	<5	0.08	<10	23	63	<10	286	4
8V3672RA/RJ	HL08-08	122739	133.00	134.50	1.50	0.62	1.2	2.06	<5	111	<0.5	<5	4.20	2	20	7	227	4.88	<1	0.38	<10	1.13	1545	34	0.02	1	1420	24	0.28	<5	5	87	<5	0.15	<10	<10	71	<10	347	3
8V3672RA/RJ	HL08-08	122740	134.50	136.00	1.50	0.66	1.7	2.17	26	114	<0.5	<5	5.14	2	22	4	185	5.29	<1	0.41	<10	1.11	1878	27	0.02	1	1454	31	0.62	<5	5	110	<5	0.14	<10	<10	66	<10	323	3
8V2415RA/RJ	HL08-08	83824	136.00	141.00	5.00	0.66	1.1	1.95	<5	85	<0.5	<5	4.14	3	15	7	179	4.44	<1	0.28	<10	0.95	1592	55	0.02	1	1244	12	0.26	<5	4	100	<5	0.12	<10	23	64	<10	307	3
8V2415RA/RJ	HL08-08	83825	141.00	142.38	1.38	0.50	1.1	2.10	<5	54	<0.5	<5	2.96	2	16	11	197	4.72	<1	0.13	<10	1.22	1769	76	0.03	1	1240	12	0.22	<5	4	114	<5	0.10	<10	24	72	<10	264	4
HL08-09 - Zone: Hammer, Pad 15: 434981E, 6223757N, Elev: 1195m, Az: 000, Dip: -50, EOH: 224.70m																																								
8V2415RA/RJ	HL08-09	83826	3.00	5.00	2.00	0.07	0.8	0.67	103	116	<0.5	<5	1.37	1	9	19	8	2.99	<1	0.28	<10	0.28	897	2	0.01	3	910	9	1.79	<5	1	40	<5	<0.01	<10	16	15	<10	39	2
8V2415RA/RJ	HL08-09	83827	5.00	7.00	2.00	0.07	2.6	0.38	124	121	<0.5	<5	6.63	2	7	26	10	2.77	<1	0.24	<10	0.31	2613	2	0.01	2	965	109	1.57	5	2	196	<5	<0.01	<10	21	8	<10	132	2
8V2415RA/RJ	HL08-09	83828	7.00	9.00	2.00	0.12	3.1	0.61	201	134	<0.5	<5	8.50	1	8	16	7	2.56	<1	0.34	<10	0.30	2731	<2	0.01	1	752	24	1.41	<5	2	183	<5	<0.01	<10	23	12	<10	40	2
8V2415RA/RJ	HL08-09	83829	9.00	11.00	2.00	0.15	8.1	1.50	619	128	<0.5	<5	3.36	2	10	19	27	3.48	<1	0.31	<10	0.80	2196	<2	0.01	3	1053	55	0.46	10	3	123	<5	<0.01	<10	21	42	<10	125	3
8V2415RA/RJ	HL08-09	83830	16.00	18.00	2.00	0.14	1.1	1.46	123	133	<0.5	<5	3.77	1	11	12	17	3.17	<1	0.39	<10	0.67	2013	<2	0.01	2	1084	9	0.58	5	3	98	<5	0.03	<10	16	36	<10	57	3
8V2415RA/RJ	HL08-09	83831	23.00	25.00	2.00	0.02	0.3	1.67	29	140	<0.5	<5	3.13	1	9	8	20	3.52	<1	0.35	<10	0.86	1811	<2	0.02	2	1099	3	0.18	<5	3	122	<5	0.01	<10	<10	41	<10	58	3
8V2415RA/RJ	HL08-09	83832	25.00	27.00	2.00	0.08	1.0	1.42	92	137	<0.5	<5	1.09	1	10	23	16	3.66	<1	0.30	<10	0.69	1343	<2	0.01	3	1003	8	0.83	<5	2	43	<5	0.01	<10	<10	44	<10	40	3
8V241																																								

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																										
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V2415RA/RJ	HL08-09	83874	121.00	122.50	1.50	0.70	12.3	1.12	259	75	<0.5	9	2.34	6	13	13	75	4.63	<1	0.36	<10	0.48	1478	2	0.01	2	1129	547	3.25	8	1	104		<0.01	<10	28	27	<10	694	3
8V2469RA/RJ	HL08-09	83875	122.50	124.00	1.50	0.37	6.0	1.43	305	44	<0.5	8	2.05	3	15	17	31	6.17	<1	0.38	<10	0.78	1767	<2	0.01	3	1086	90	4.78	15	2	79	<5	<0.01	<10	33	37	<10	201	4
8V2469RA/RJ	HL08-09	83876	124.00	125.40	1.40	0.46	4.3	0.68	179	110	<0.5	<5	0.73	4	9	58	54	2.81	<1	0.31	<10	0.25	595	7	0.01	3	732	376	1.94	7	1	26	<5	<0.01	<10	12	18	<10	514	2
8V2469RA/RJ	HL08-09	83877	125.40	126.60	1.20	0.10	1.0	1.68	104	84	<0.5	<5	2.00	2	15	13	6	5.25	<1	0.25	<10	1.27	2191	9	0.01	2	1262	46	2.72	<5	3	66	<5	<0.01	<10	23	70	<10	143	3
8V2469RA/RJ	HL08-09	83878	126.60	127.75	1.15	0.17	1.8	1.12	164	67	<0.5	<5	1.68	3	14	30	3	5.01	<1	0.22	<10	0.96	1836	7	0.01	3	1063	163	3.29	<5	2	78	<5	0.01	<10	23	55	<10	244	3
8V2469RA/RJ	HL08-09	83879	127.75	129.50	1.75	0.18	1.8	0.57	120	82	<0.5	<5	10.05	2	6	24	6	2.50	<1	0.17	<10	0.44	2830	3	0.01	2	453	81	1.28	<5	2	215	<5	<0.01	<10	20	18	<10	145	1
8V2469RA/RJ	HL08-09	83880	129.50	131.50	2.00	0.09	0.6	2.37	21	228	<0.5	<5	5.73	1	15	10	42	4.31	<1	0.66	<10	0.95	1071	<2	0.02	2	1124	22	0.61	5	5	156	<5	0.01	<10	20	65	<10	83	3
8V2469RA/RJ	HL08-09	83881	131.50	133.50	2.00	0.11	0.3	2.23	20	181	<0.5	<5	6.28	1	15	9	29	4.02	<1	0.46	<10	1.10	2158	<2	0.05	2	1121	14	0.44	<5	5	131	<5	0.07	<10	21	72	<10	77	3
8V2469RA/RJ	HL08-09	83882	133.50	135.50	2.00	0.02	0.4	1.81	46	102	<0.5	<5	3.60	1	13	15	18	4.02	<1	0.32	<10	1.03	1857	<2	0.03	2	1155	8	0.65	<5	4	125	<5	0.02	<10	18	54	<10	59	3
8V2469RA/RJ	HL08-09	83883	135.50	137.50	2.00	0.02	0.3	2.28	25	104	<0.5	<5	2.88	1	16	7	35	5.11	<1	0.27	<10	1.33	2023	<2	0.03	2	1274	5	0.53	<5	4	118	<5	0.03	<10	21	75	<10	81	3
8V2469RA/RJ	HL08-09	83884	137.50	139.50	2.00	0.02	0.5	2.83	12	96	<0.5	<5	2.85	2	20	8	73	6.20	<1	0.27	<10	1.74	2304	<2	0.02	3	1388	2	0.41	5	4	128	<5	0.01	<10	27	81	<10	111	4
8V2469RA/RJ	HL08-09	83885	139.50	141.50	2.00	0.01	0.3	2.30	16	106	<0.5	<5	3.28	1	18	7	61	5.17	<1	0.29	<10	1.30	1983	<2	0.02	3	1260	4	0.52	<5	4	135	<5	<0.01	<10	21	61	<10	84	3
8V2469RA/RJ	HL08-09	83886	141.50	143.50	2.00	0.01	0.5	1.77	18	124	<0.5	<5	4.22	1	14	13	51	4.22	<1	0.28	<10	1.08	2100	<2	0.03	2	1173	6	0.98	6	3	153	<5	0.01	<10	22	49	<10	65	3
8V2469RA/RJ	HL08-09	83887	152.00	154.00	2.00	0.01	0.4	1.83	9	136	<0.5	<5	4.41	1	15	5	41	3.96	<1	0.33	<10	1.00	1801	<2	0.01	2	1282	34	0.38	<5	3	165	<5	0.08	<10	16	42	<10	93	3
8V2469RA/RJ	HL08-09	83888	154.00	156.00	2.00	0.01	0.3	1.62	11	232	<0.5	<5	4.50	1	14	11	41	3.90	<1	0.33	<10	0.84	1705	<2	0.02	2	1204	6	0.68	<5	3	192	<5	0.04	<10	14	40	<10	59	3
8V2469RA/RJ	HL08-09	83889	156.00	158.00	2.00	0.01	0.1	1.62	<5	385	<0.5	<5	2.99	1	14	7	24	3.96	<1	0.33	<10	0.97	1534	<2	0.02	2	1260	2	0.41	<5	3	207	<5	0.02	<10	14	37	<10	59	4
8V2469RA/RJ	HL08-09	83890	158.00	160.00	2.00	0.01	0.2	0.64	<5	158	<0.5	<5	3.94	1	10	46	9	3.13	<1	0.37	<10	0.74	1710	<2	0.02	2	1028	<2	0.37	<5	3	307	<5	<0.01	<10	18	15	<10	31	2
8V2469RA/RJ	HL08-09	83891	182.50	184.50	2.00	0.02	0.3	1.57	49	105	<0.5	<5	5.47	1	14	7	23	4.07	<1	0.33	<10	0.85	1947	<2	0.02	2	1160	6	1.29	5	4	171	<5	0.02	<10	19	47	<10	48	3
8V2469RA/RJ	HL08-09	83892	194.00	196.06	2.06	0.02	0.2	1.47	33	89	<0.5	<5	8.42	1	10	15	19	3.24	<1	0.34	<10	0.80	2141	<2	0.02	2	1164	19	0.67	<5	3	255	<5	0.03	<10	20	39	<10	44	3
8V2469RA/RJ	HL08-09	83893	196.06	198.00	1.94	0.04	0.5	1.61	67	100	<0.5	<5	6.87	1	12	8	27	3.49	<1	0.35	<10	0.88	2236	<2	0.02	2	1217	21	1.11	<5	3	218	<5	0.05	<10	20	43	<10	59	3
8V2469RA/RJ	HL08-09	83894	209.80	210.80	1.00	0.05	0.9	0.87	121	100	<0.5	<5	4.49	1	17	31	40	4.07	<1	0.35	<10	0.71	1768	<2	0.01	2	1184	16	2.18	5	2	297	<5	<0.01	<10	24	22	<10	42	2
8V2469RA/RJ	HL08-09	83895	215.00	216.00	1.00	0.07	1.1	1.52	73	123	<0.5	<5	4.77	2	22	8	81	5.16	<1	0.47	<10	0.95	1913	<2	0.01	3	1140	8	1.93	<5	3	189	<5	<0.01	<10	24	34	<10	47	3
8V2469RA/RJ	HL08-09	83896	218.70	220.70	2.00	0.16	1.4	1.57	88	116	<0.5	<5	3.89	4	15	19	25	4.05	<1	0.39	<10	0.74	1926	<2	0.01	2	1155	40	1.30	<5	2	284	<5	<0.01	<10	24	34	<10	402	2
8V2469RA/RJ	HL08-09	83897	220.70	222.70	2.00	0.06	1.0	1.43	63	101	<0.5	<5	4.88	1	13	15	27	3.78	<1	0.37	<10	0.60	1997	<2	0.01	2	1083	13	1.34	<5	2	198	<5	<0.01	<10	25	33	<10	79	2
8V2469RA/RJ	HL08-09	83898	222.70	224.70	2.00	0.31	1.9	1.32	77	122	<0.5	<5	1.43	1	15	20	36	3.50	<1	0.43	<10	0.51	1051	<2	0.01	2	1312	11	1.52	<5	2	47	<5	0.01	<10	12	27	<10	59	2
HL08-10 - Zone: 49er, Pad 16: 435267E, 6223371N, Elev: 1253m, Az: 220, Dip: -50, EOH: 214.94m																																								
8V2469RA/RJ	HL08-10	83899	1.53	3.40	1.87	0.37	3.0	0.43	148	125	<0.5	<5	0.39	2	7	78	71	2.53	<1	0.21	<10	0.20	604	21	0.01	4	604	54	1.33	7	1	35	<5	<0.01	<10	<10	11	<10	208	2
8V2469RA/RJ	HL08-10	83900	3.40	5.40	2.00	0.88	5.4	1.21	372	96	<0.5	<5	0.22	3	11	76	221	4.57	<1	0.16	<10	0.68	1353	22	0.01	4	640	28	1.84	13	4	9	<5	0.01	<10	14	75	<10	197	3
8V2469RA/RJ	HL08-10	83901	5.40	7.40	2.00	0.52	4.0	1.63	91	109	<0.5	<5	0.28	3	14	47	191	4.63	<1	0.17	<10	1.01	1838	12	0.01	4	799	20	1.12	6	4	11	<5	0.01	<10	16	106	<10	257	3
8V2469RA/RJ	HL08-10	83902	7.40	8.50	1.10	0.70	5.5	1.88	91	118	<0.5	<5	0.21	3	14	55	330	5.18	<1	0.18	<10	1.29	2036	8	0.01	5	855	12	1.21	8	5	6	<5	<0.01	<10	17	130	<10	274	3
8V2469RA/RJ	HL08-10	83903	8.50	9.79	1.29	0.47	5.8	2.04	75	121	<0.5	<5	0.35	3	18	35	392	5.21	<1	0.30	<10	1.24	2055	10	0.01	5	1069	12	1.20	7	5	14	<5	<0.01	<10	19	102	<10	291	3
8V2469RA/RJ	HL08-10	83904	9.79	11.84	2.05	0.34	4.8	1.03	191	109	<0.5	<5	0.27	3	15	86	279	4.70	<1	0.24	<10	0.57	1003	11	0.01	6	788	146	2.67	8	3	15	<5	<0.01	<10	12	65	<10	258	3
8V2469RA/RJ	HL08-10	83905	11.84	13.65	1.81	0.87	4.6	1.24	146	134	<0.5	<5	0.41	3	16	48	228	4.89	<1	0.29	<10	0.63	1532	15	0.01	4	1123	18	2.16	9	4	19	<5	<0.01	<10	11	79	<10	229	3
8V2469RA/RJ	HL08-10	83906	13.65	15.52	1.87	0.29	3.5	1.25	143	135	<0.5	<5	0.42	3	14	95	173	4.34	<1	0.27	<10	0.65	1525	17	0.01	5	931	26	1.47	6	3	23	<5	<0.01	<10	14	64	<10	207	3
8V2469RA/RJ	HL08-10	83907	15.52	16.55	1.03	0.35	3.4	0.87	669	128	<0.5	<5	0.87	3	12	58	148	4.42	<1	0.27	<10	0																		

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																											
					0.5-1.0	1.0-3.0	3.0-5.0	>5.0	5-10	10-50	50-100	>100	2500-5000	5000-10000	>10000	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Zr													
8V2469RA/RJ	HL08-10	83944	83.29	85.02	1.73	0.10	1.3	0.33	102	121	<0.5	<5	3.08	1	7	128	21	2.86	<1	0.25	<10	0.41	1285	8	0.01	4	561	23	1.47	6	2	101	10	<0.01	32	28	8	<10	76	2
8V2469RA/RJ	HL08-10	83945	85.02	86.50	1.48	0.08	1.2	0.77	110	145	<0.5	<5	2.60	1	6	41	8	2.79	<1	0.35	<10	0.45	1104	<2	0.01	2	769	12	1.35	<5	1	75	11	<0.01	30	26	18	<10	52	4
8V2469RA/RJ	HL08-10	83946	86.50	88.00	1.50	0.52	14.7	10.2	175	107	<0.5	<5	1.89	5	8	76	29	4.08	<1	0.35	<10	0.53	1105	2	0.01	4	843	700	2.10	5	2	61	<5	<0.01	<10	16	27	<10	620	4
8V2469RA/RJ	HL08-10	83947	88.00	89.24	1.24	0.07	0.4	1.14	46	156	<0.5	<5	2.96	1	8	106	19	3.83	<1	0.27	<10	0.74	1443	3	0.01	5	751	10	1.03	<5	3	139	<5	<0.01	<10	15	30	<10	101	3
8V2472RA/RJ	HL08-10	83948	89.24	90.80	1.56	0.06	1.2	0.59	49	119	<0.5	<5	2.80	3	8	74	<1	3.47	<1	0.37	<10	0.70	1413	5	0.02	4	899	16	0.79	5	3	185	<5	<0.01	<10	14	12	<10	203	3
8V2472RA/RJ	HL08-10	83949	90.80	92.79	1.99	0.09	1.6	0.72	46	135	<0.5	<5	2.52	2	7	134	<1	3.86	<1	0.35	<10	0.54	1419	6	0.02	5	828	17	0.59	6	4	113	<5	<0.01	<10	16	17	<10	123	3
8V2472RA/RJ	HL08-10	83950	92.79	94.70	1.91	0.09	1.1	1.16	34	88	<0.5	<5	1.94	1	8	93	34	3.78	<1	0.26	<10	0.76	1196	3	0.02	4	809	7	0.82	5	4	67	<5	0.01	<10	15	35	<10	118	3
8V2472RA/RJ	HL08-10	83951	94.70	96.70	2.00	0.12	1.0	1.50	36	107	<0.5	<5	1.98	3	8	105	24	3.87	<1	0.28	<10	0.77	1331	6	0.03	4	901	23	0.55	5	3	62	<5	<0.01	<10	12	43	<10	368	3
8V2472RA/RJ	HL08-10	83952	96.70	98.70	2.00	0.16	3.7	1.10	87	72	<0.5	<5	3.43	2	9	86	54	3.57	<1	0.28	<10	0.65	1555	9	0.01	5	837	19	1.59	5	2	97	<5	<0.01	<10	21	31	<10	228	3
8V2472RA/RJ	HL08-10	83953	98.70	100.00	1.30	0.30	1.2	1.39	52	71	<0.5	<5	2.37	2	9	93	30	3.96	<1	0.25	<10	0.78	1316	11	0.02	6	781	6	1.11	<5	3	74	<5	<0.01	<10	17	52	<10	98	3
8V2472RA/RJ	HL08-10	83954	100.00	101.50	1.50	0.21	1.3	1.24	83	69	<0.5	<5	3.21	1	11	89	95	4.11	<1	0.32	<10	0.80	1393	11	0.01	6	897	6	1.82	5	3	108	<5	<0.01	<10	17	39	<10	70	3
8V2472RA/RJ	HL08-10	83955	101.50	103.40	1.90	0.18	1.3	0.72	107	63	<0.5	<5	4.35	2	11	88	58	3.93	<1	0.33	<10	0.74	1933	6	0.01	5	780	138	1.46	<5	3	299	<5	<0.01	<10	23	15	<10	87	2
8V2472RA/RJ	HL08-10	83955A	Blank	Blank	<0.01	<0.1	1.04	<5	237	<0.5	<5	0.54	<1	6	132	<1	2.10	<1	0.52	<10	0.61	568	<2	0.09	7	738	<2	<0.01	<5	2	58	5	0.13	<10	<10	38	<10	49	3	
8V2472RA/RJ	HL08-10	83956	103.40	105.40	2.00	0.27	1.3	1.19	52	196	<0.5	<5	2.55	4	9	112	45	3.38	<1	0.23	<10	0.74	1241	13	0.02	5	687	278	1.04	5	3	113	<5	0.01	<10	17	38	<10	330	3
8V2472RA/RJ	HL08-10	83957	105.40	107.00	1.60	0.21	1.3	1.81	89	173	<0.5	<5	2.84	2	13	63	87	4.92	<1	0.30	<10	1.08	1484	15	0.02	6	965	8	1.59	5	4	93	<5	0.02	<10	20	61	<10	115	4
8V2472RA/RJ	HL08-10	83958	107.00	109.00	2.00	0.23	1.4	1.87	24	211	<0.5	<5	3.19	3	13	81	51	4.49	<1	0.22	<10	1.12	1402	9	0.03	7	915	185	0.60	<5	4	104	<5	0.03	<10	20	70	<10	235	4
8V2472RA/RJ	HL08-10	83959	109.00	111.00	2.00	0.13	1.0	1.51	21	91	<0.5	<5	5.23	4	10	43	17	4.04	<1	0.20	<10	0.88	1792	4	0.03	4	827	13	0.65	<5	3	133	<5	0.01	<10	19	61	<10	357	2
8V2472RA/RJ	HL08-10	83960	111.00	113.00	2.00	0.15	0.9	1.78	23	108	<0.5	<5	3.17	2	12	51	26	4.61	<1	0.26	<10	1.06	1368	5	0.03	5	1013	5	0.57	<5	4	91	<5	0.01	<10	20	71	<10	105	3
8V2472RA/RJ	HL08-10	83961	113.00	114.65	1.65	0.05	0.7	1.40	14	129	<0.5	<5	2.63	1	10	42	22	3.86	<1	0.18	<10	0.77	1183	5	0.03	4	886	4	0.50	<5	4	79	<5	0.03	<10	15	64	<10	108	3
8V2472RA/RJ	HL08-10	83962	114.65	116.30	1.65	0.10	1.4	0.44	26	321	<0.5	<5	1.54	2	13	88	66	4.64	<1	0.31	<10	0.71	1321	7	0.02	5	1015	9	0.61	5	3	73	<5	<0.01	<10	19	29	<10	105	2
8V2472RA/RJ	HL08-10	83963	116.30	118.00	1.70	0.14	1.8	1.17	24	61	<0.5	<5	4.98	1	10	48	63	3.88	<1	0.23	<10	0.73	1654	8	0.03	4	844	7	0.66	<5	3	142	<5	<0.01	<10	18	49	<10	121	2
8V2472RA/RJ	HL08-10	83964	118.00	119.40	1.40	0.23	1.7	1.42	43	72	<0.5	<5	4.96	2	12	62	141	4.50	<1	0.23	<10	0.76	1957	17	0.03	5	928	12	0.79	<5	4	138	<5	<0.01	<10	23	64	<10	181	3
8V2472RA/RJ	HL08-10	83965	119.40	120.67	1.27	0.13	2.0	1.80	33	76	<0.5	<5	3.19	3	13	42	193	2.58	<1	0.22	<10	1.00	1628	5	0.04	5	1016	47	1.05	<5	5	84	<5	0.01	<10	22	84	<10	203	3
8V2472RA/RJ	HL08-10	83966	120.67	122.41	1.74	0.03	2.0	0.83	17	122	<0.5	<5	3.82	2	11	79	171	4.72	<1	0.29	<10	0.99	1840	11	0.03	5	969	8	0.60	6	4	143	<5	<0.01	<10	20	41	<10	137	3
8V2472RA/RJ	HL08-10	83967	122.41	123.90	1.49	0.04	1.1	0.91	15	72	<0.5	<5	2.48	2	11	93	111	3.92	<1	0.24	<10	0.74	1377	7	0.03	6	941	7	0.51	5	4	81	<5	<0.01	<10	17	45	<10	144	2
8V2472RA/RJ	HL08-10	83968	123.90	125.30	1.40	0.13	1.4	0.52	45	230	<0.5	<5	1.67	3	13	156	55	4.35	<1	0.33	<10	0.75	1359	7	0.03	8	1031	107	1.09	8	4	79	<5	<0.01	<10	19	27	<10	250	3
8V2472RA/RJ	HL08-10	83969	125.30	126.25	0.95	0.09	3.4	0.97	110	62	<0.5	<5	2.98	7	11	92	58	4.31	<1	0.31	<10	0.75	1797	3	0.02	6	859	845	1.67	7	3	58	<5	<0.01	<10	22	39	<10	776	2
8V2472RA/RJ	HL08-10	83970	126.25	127.18	0.93	0.12	2.4	0.42	161	73	<0.5	<5	3.80	2	9	123	44	3.80	<1	0.31	<10	0.41	1910	7	0.01	6	780	55	2.31	8	3	71	<5	<0.01	<10	19	17	<10	199	2
8V2472RA/RJ	HL08-10	83971	127.18	129.18	2.00	0.16	1.7	1.55	17	114	<0.5	<5	3.24	2	12	35	156	4.08	<1	0.24	<10	1.01	1630	4	0.02	4	1038	8	0.37	<5	5	102	<5	0.05	<10	14	68	<10	165	3
8V2472RA/RJ	HL08-10	83972	129.18	131.18	2.00	0.20	3.0	0.75	39	97	<0.5	<5	3.17	2	11	48	264	3.87	<1	0.27	<10	0.63	1703	8	0.01	4	945	13	1.12	<5	4	68	<5	<0.01	<10	17	33	<10	143	2
8V2472RA/RJ	HL08-10	83973	131.18	133.18	2.00	0.14	2.3	1.13	123	162	<0.5	<5	5.16	3	12	33	172	4.32	<1	0.26	<10	0.77	2355	11	0.01	3	949	110	1.30	<5	3	127	<5	<0.01	<10	22	43	<10	222	3
8V2472RA/RJ	HL08-10	83974	133.18	135.18	2.00	0.12	3.6	1.39	91	112	<0.5	<5	3.75	2	14	37	222	4.67	<1	0.24	<10	1.02	2173	18	0.01	3	1085	19	1.35	<5	4	133	<5	<0.01	<10	21	66	<10	158	3
8V2472RA/RJ	HL08-10	83975	135.18	137.18	2.00	0.12	3.2	0.30	120	44	<0.5	<5	4.00	2	11	70	129	3.78	<1	0.25	<10	0.74	2056	9	0.01	2	856	30	1.41	6	4	185	<5	<0.01	<10	22	15	<10	156	2
8V2472RA/RJ	HL08-10	83976	137.18	139.18	2.00	0.12	1.7	0.93	78	157	<0.5	<5	3.65	2	16	40	89	5.00	<1	0.28	<10	0.74	1769	6	0.01	3	1159	27	1.20	<5	4	113	<5	<0.01	<10	21	57	<10	148	3
8V2472RA/RJ	HL08-10	83977	139.18	140.13	0.95	0.10	3.4	0.59	99	90	<																													

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:				S				Sb				Sc				Sr				Th				Ti				U				V				W				Zn				Zr			
						0.5-1.0	1.0-3.0	3.0-5.0	>5.0	5-10	10-50	50-100	>100	2500-5000	5000-10000	>10000	2500-5000	5000-10000	>10000	2500-5000	5000-10000	>10000	2500-5000	5000-10000	>10000	2500-5000	5000-10000	>10000	2500-5000	5000-10000	>10000	2500-5000	5000-10000	>10000	2500-5000	5000-10000	>10000	2500-5000	5000-10000	>10000	2500-5000	5000-10000	>10000																		
8V2472RA/RJ	HL08-10	84013	181.79	183.79	2.00	0.02	0.9	0.89	23	63	<0.5	<5	3.63	2	7	77	38	3.98	<1	0.20	<10	0.84	1915	21	0.02	4	834	67	0.71	5	4	294	<5	<0.01	<10	12	20	<10	142	2																					
8V2472RA/RJ	HL08-10	84014	183.79	184.79	1.00	0.03	0.5	1.05	24	73	<0.5	<5	3.28	3	7	51	29	3.83	<1	0.22	<10	0.78	1548	21	0.02	3	854	17	0.64	<5	4	388	<5	<0.01	<10	11	26	<10	243	2																					
8V2472RA/RJ	HL08-10	84015	184.79	186.43	1.64	<0.01	0.4	1.44	21	88	<0.5	<5	2.77	3	8	63	33	4.02	<1	0.21	<10	0.81	1471	7	0.02	3	897	47	0.63	<5	4	142	<5	<0.01	<10	11	36	<10	288	3																					
8V2472RA/RJ	HL08-10	84016	186.43	186.93	0.50	<0.01	<0.1	0.87	<5	426	<0.5	<5	2.58	1	6	37	<1	1.97	<1	0.25	16	5.7	477	<2	0.03	4	879	16	0.06	<5	2	120	<5	<0.01	<10	<10	21	<10	48	4																					
8V2472RA/RJ	HL08-10	84017	190.85	191.85	1.00	0.13	0.6	1.14	23	72	<0.5	<5	3.93	1	7	51	48	3.10	<1	0.19	<10	0.64	1335	33	0.01	3	854	139	0.58	<5	3	125	<5	<0.01	<10	11	26	<10	98	2																					
8V2472RA/RJ	HL08-10	84018	191.85	193.65	1.80	0.12	1.0	1.31	119	300	<0.5	<5	3.49	2	8	42	62	3.57	<1	0.19	<10	0.76	1566	6	0.01	3	901	67	0.75	5	3	89	<5	<0.01	<10	12	36	<10	165	2																					
8V2472RA/RJ	HL08-10	84019	193.65	194.15	0.50	0.02	<0.1	0.99	8	58	<0.5	<5	3.01	1	6	42	<1	2.14	<1	0.26	<10	0.64	874	<2	0.02	5	689	3	0.36	<5	3	114	<5	<0.01	<10	<10	21	<10	42	3																					
8V2472RA/RJ	HL08-10	84020	197.40	198.10	0.70	0.01	<0.1	1.28	<5	427	0.5	<5	2.81	1	8	62	26	3.25	<1	0.33	11	0.92	942	36	0.03	3	762	7	0.19	<5	5	117	<5	0.02	<10	<10	49	<10	92	3																					
8V2472RA/RJ	HL08-10	84021	198.10	198.60	0.50	<0.01	<0.1	0.91	<5	898	<0.5	<5	2.55	<1	5	51	<1	1.69	<1	0.25	12	0.62	536	<2	0.03	5	633	2	0.09	<5	2	107	<5	<0.01	<10	<10	19	<10	34	4																					
8V2472RA/RJ	HL08-10	84022	209.98	214.00	4.02	0.11	0.9	1.64	10	106	<0.5	<5	2.66	1	13	29	158	3.79	<1	0.21	<10	0.91	1257	45	0.02	4	1024	9	0.27	<5	3	67	<5	0.10	<10	11	67	<10	111	3																					
8V2472RA/RJ	HL08-10	84023	214.00	214.94	0.94	0.09	0.5	1.80	<5	92	<0.5	<5	2.92	1	13	30	197	4.50	<1	0.14	<10	0.92	1439	15	0.03	4	1020	3	0.09	<5	3	65	<5	0.10	<10	16	72	<10	143	3																					
HL08-11 - Zone: 49er, Pad 16: 435267E, 6223371N, Elev: 1253m, Az: 220, Dip: -70, EOH: 141.77m																																																													
8V2472RA/RJ	HL08-11	84024	1.22	3.22	2.00	0.28	6.4	0.31	549	131	<0.5	<5	0.20	4	6	68	59	2.38	<1	0.16	<10	0.15	394	19	0.01	3	467	335	1.57	11	1	4	<5	<0.01	<10	<10	10	<10	498	2																					
8V2472RA/RJ	HL08-11	84025	3.22	5.22	2.00	0.42	6.6	0.71	164	122	<0.5	<5	0.34	3	9	52	177	3.92	<1	0.18	<10	0.47	1084	15	0.01	3	812	22	1.82	6	2	10	<5	<0.01	<10	10	35	<10	216	3																					
8V2472RA/RJ	HL08-11	84026	Blank	Blank	Blank	<0.01	<0.1	0.90	<5	226	<0.5	<5	0.42	<1	6	109	<1	2.04	<1	0.49	<10	0.57	534	<2	0.07	6	738	2	<0.01	<5	2	32	5	0.12	<10	<10	36	<10	45	2																					
8V2472RA/RJ	HL08-11	84027	Std	PM1112	Blank	1.36	226.9	0.69	1914	89	<0.5	63	3.85	2	57	20	2337	2.86	1	0.08	<10	0.22	781	130	0.05	23	804	374	0.63	460	1	122	<5	0.02	<10	11	16	19	280	7																					
8V2472RA/RJ	HL08-11	84028	5.22	7.22	2.00	0.62	7.0	1.21	277	84	<0.5	6	3.00	6	16	45	298	5.03	<1	0.21	<10	0.63	1263	18	0.01	5	891	56	2.52	9	3	4	<5	<0.01	<10	14	74	<10	513	3																					
8V2472RA/RJ	HL08-11	84029	7.22	9.22	2.00	0.62	4.8	1.40	198	100	<0.5	6	0.27	3	14	44	173	5.03	<1	0.21	<10	0.68	1483	20	0.01	4	887	34	2.04	8	4	3	<5	<0.01	<10	15	86	<10	318	3																					
8V2472RA/RJ	HL08-11	84030	9.22	11.22	2.00	0.63	4.2	1.70	102	115	<0.5	5	0.52	3	16	38	247	5.03	<1	0.22	<10	0.99	1919	17	0.01	5	1010	36	1.18	<5	5	17	<5	<0.01	<10	14	95	<10	241	3																					
8V2472RA/RJ	HL08-11	84031	11.22	13.22	2.00	0.43	4.0	0.83	156	106	<0.5	<5	0.55	2	14	51	288	4.28	<1	0.22	<10	0.66	1533	11	0.01	4	797	27	1.34	5	3	26	<5	<0.01	<10	15	44	<10	179	2																					
8V2472RA/RJ	HL08-11	84032	13.22	15.22	2.00	0.33	3.3	0.66	170	128	<0.5	<5	0.57	4	9	65	158	3.64	<1	0.17	<10	0.50	1423	14	0.01	3	718	41	1.47	6	2	27	<5	<0.01	<10	34	<10	397	2																						
8V2472RA/RJ	HL08-11	84033	15.22	17.20	1.98	0.50	4.7	0.86	279	120	<0.5	6	0.93	2	12	46	257	4.32	<1	0.18	<10	0.60	1894	16	0.01	3	930	25	1.61	6	4	34	<5	<0.01	<10	15	48	<10	201	3																					
8V2472RA/RJ	HL08-11	84034	17.20	18.20	1.00	0.32	6.2	0.24	316	32	<0.5	13	0.66	4	10	71	175	8.27	<1	0.22	<10	0.24	871	10	0.01	4	779	45	>5.00	22	2	29	<5	<0.01	<10	28	14	<10	134	5																					
8V2472RA/RJ	HL08-11	84035	18.20	19.20	1.00	0.23	3.6	0.25	203	87	<0.5	6	0.68	5	14	68	101	4.15	<1	0.23	<10	0.40	1349	5	0.01	4	853	35	2.34	8	2	39	<5	<0.01	<10	16	15	<10	495	2																					
8V2472RA/RJ	HL08-11	84036	19.20	21.20	2.00	0.29	3.3	0.26	173	118	<0.5	5	1.53	3	12	70	133	4.05	<1	0.20	<10	0.53	1494	12	0.01	4	838	37	2.17	7	3	132	<5	<0.01	<10	17	16	<10	237	2																					
8V2472RA/RJ	HL08-11	84037	21.20	23.00	1.80	0.35	3.4	0.29	141	104	<0.5	<5	0.59	3	12	93	157	3.45	<1	0.20	<10	0.32	939	8	0.01	4	769	19	1.89	7	2	45	<5	<0.01	<10	12	18	<10	313	2																					
8V2472RA/RJ	HL08-11	84038	23.00	24.40	1.40	0.37	2.1	0.58	119	169	<0.5	5	0.67	3	16	41	116	4.82	<1	0.28	<10	0.67	2174	18	0.01	4	1113	25	1.33	7	4	38	5	<0.01	<10	16	32	<10	282	3																					
8V2472RA/RJ	HL08-11	84039	24.40	25.45	1.05	0.89	5.1	0.42	268	114	<0.5	<5	0.60	4	13	63	110	4.37	<1	0.20	<10	0.44	1473	11	0.01	3	887	36	2.31	7	3	44	<5	<0.01	<10	16	31	<10	461	2																					
8V2472RA/RJ	HL08-11	84040	25.45	26.60	1.15	0.71	8.4	0.35	391	60	<0.5	7	0.18	40	10	75	117	4.96	<1	0.19	<10	0.15	298	6	<0.01	3	523	2171	4.82	8	1	<1	<5	<0.01	<10	14	18	<10	513	3																					
8V2472RA/RJ	HL08-11	84041	26.60	27.50	0.90	0.25	17.9	0.21	238	40	<0.5	10	0.15	80	6	94	173	5.78	<1	0.14	<10	0.10	227	5	<0.01	3	345	8036	>5.00	10	<1	3	<5	<0.01	<10	15	6	<10	9300	3																					
8V2472RA/RJ	HL08-11	84042	27.50	28.50	1.00	0.15																																																							

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V2472RA/RJ	HL08-11	84082	89.65	90.09	0.44	0.10	2.6	0.59	124	46	<0.5	11	1.41	6	7	105	35	4.08	<1	0.17	<10	0.67	1253	3	0.01	4	642	1555	>5.00	12	2	63	<5	<0.01	<10	23	22	<10	462	5
8V2472RA/RJ	HL08-11	84083	90.09	90.65	0.56	0.10	0.9	0.54	34	62	<0.5	5	1.20	8	8	72	32	4.38	<1	0.21	<10	0.56	967	2	0.01	3	858	78	1.88	6	2	50	<5	<0.01	<10	14	<10	984	3	
8V2472RA/RJ	HL08-11	84084	90.65	91.65	1.00	0.05	0.2	0.84	30	61	<0.5	<5	0.81	1	7	93	5	3.45	<1	0.19	<10	0.58	856	4	0.01	3	789	11	0.84	5	2	33	<5	<0.01	<10	<10	23	<10	82	2
8V2472RA/RJ	HL08-11	84085	Blank	Blank		0.01	<0.1	0.93	<5	229	<0.5	<5	0.43	<1	6	114	<1	2.15	<1	0.49	<10	0.58	540	<2	0.07	6	721	2	0.01	<5	2	43	<5	0.12	<10	<10	37	<10	47	2
8V2472RA/RJ	HL08-11	84086	Std	PM1110		1.80	175.3	0.74	213	180	<0.5	110	4.73	3	16	21	4169	3.39	5	0.18	<10	0.19	562	82	0.03	36	653	224	1.44	279	2	182	<5	0.05	<10	<10	19	25	260	9
8V2472RA/RJ	HL08-11	84087	91.65	92.65	1.00	0.05	0.3	0.82	62	47	<0.5	<5	0.99	2	7	85	20	4.49	<1	0.17	<10	0.62	976	3	0.01	3	738	8	2.12	10	2	42	<5	<0.01	<10	14	28	<10	76	3
8V2472RA/RJ	HL08-11	84088	92.65	94.65	2.00	0.07	0.4	0.65	62	46	<0.5	<5	0.99	1	7	94	10	3.86	<1	0.18	<10	0.57	891	2	0.01	4	629	7	1.68	6	2	40	<5	<0.01	<10	11	24	<10	48	2
8V2472RA/RJ	HL08-11	84089	94.65	96.22	1.57	0.07	0.2	0.88	42	140	<0.5	<5	1.81	1	8	75	8	3.77	<1	0.23	<10	0.74	1219	10	0.01	3	860	7	0.95	<5	3	66	<5	<0.01	<10	<10	32	<10	60	2
8V2472RA/RJ	HL08-11	84090	96.22	97.75	1.53	0.10	0.2	0.28	49	77	<0.5	<5	1.72	2	8	108	13	3.70	<1	0.19	<10	0.61	1288	2	0.01	4	761	6	0.76	<5	3	87	<5	<0.01	<10	<10	19	<10	97	2
8V2472RA/RJ	HL08-11	84091	97.75	99.75	2.00	0.05	0.5	0.27	33	164	<0.5	<5	1.84	2	8	108	18	3.89	<1	0.21	<10	0.69	1305	5	0.01	3	795	6	0.90	5	3	113	<5	<0.01	<10	12	18	<10	90	2
8V2472RA/RJ	HL08-11	84092	99.75	101.75	2.00	0.09	0.3	0.24	50	151	<0.5	<5	1.82	2	7	143	19	3.82	<1	0.18	<10	0.64	1185	5	0.01	4	676	5	1.14	7	3	110	<5	<0.01	<10	13	16	<10	80	2
8V2472RA/RJ	HL08-11	84093	101.75	103.03	1.28	0.16	0.9	0.24	63	76	<0.5	6	1.96	3	7	99	72	4.78	<1	0.20	<10	0.62	1154	2	0.01	4	713	19	2.38	6	3	108	<5	<0.01	<10	17	15	<10	175	3
8V2472RA/RJ	HL08-11	84094	103.03	105.03	2.00	0.07	0.1	0.31	32	57	<0.5	<5	1.84	1	8	97	14	3.86	<1	0.22	<10	0.71	1224	4	0.02	3	828	5	0.63	<5	3	99	<5	<0.01	<10	10	23	<10	69	2
8V2472RA/RJ	HL08-11	84095	105.03	106.83	1.80	0.21	0.3	0.25	37	248	<0.5	<5	2.40	2	7	93	19	3.43	<1	0.20	<10	0.65	1124	6	0.01	3	672	10	0.87	<5	2	130	<5	<0.01	<10	<10	15	<10	81	2
8V2472RA/RJ	HL08-11	84096	106.83	108.83	2.00	0.09	0.2	0.93	15	90	<0.5	<5	3.62	2	9	76	38	4.03	<1	0.17	<10	0.73	1508	5	0.02	3	890	7	0.41	<5	4	153	<5	<0.01	<10	13	43	<10	91	2
8V2472RA/RJ	HL08-11	84097	108.83	110.83	2.00	0.11	0.1	1.12	8	103	<0.5	<5	2.74	1	9	59	22	3.97	<1	0.18	<10	0.75	1172	3	0.02	3	929	6	0.37	<5	3	89	<5	<0.01	<10	<10	46	<10	79	2
8V2472RA/RJ	HL08-11	84098	110.83	112.83	2.00	0.12	0.1	1.09	24	69	<0.5	<5	2.24	2	9	68	22	3.92	<1	0.22	<10	0.73	1101	17	0.02	3	966	5	0.80	5	3	63	<5	<0.01	<10	<10	40	<10	124	2
8V2472RA/RJ	HL08-11	84099	112.83	114.56	1.73	0.18	0.4	1.17	24	49	<0.5	5	1.80	2	11	47	9	5.17	<1	0.16	<10	0.82	1055	3	0.02	4	1057	5	1.73	5	3	60	<5	<0.01	<10	13	48	<10	153	3
8V2472RA/RJ	HL08-11	84100	114.56	116.20	1.64	0.23	0.2	0.49	340	98	<0.5	5	2.13	2	13	73	12	4.76	<1	0.27	<10	0.76	1484	5	0.02	3	1156	8	0.61	5	3	111	<5	<0.01	<10	13	28	<10	193	3
8V2472RA/RJ	HL08-11	84101	116.20	118.20	2.00	0.25	0.2	1.34	31	75	<0.5	<5	2.43	2	12	39	14	4.66	<1	0.22	<10	0.93	1246	4	0.02	3	1110	5	0.62	<5	3	88	<5	<0.01	<10	10	50	<10	120	2
8V2472RA/RJ	HL08-11	84102	118.20	119.20	1.00	0.22	<0.1	1.14	22	88	<0.5	<5	3.62	2	11	52	22	4.34	<1	0.21	<10	0.82	1295	7	0.02	3	1083	5	0.57	<5	3	117	<5	<0.01	<10	10	47	<10	188	3
8V2472RA/RJ	HL08-11	84103	119.20	121.16	1.96	0.23	0.3	0.41	24	186	<0.5	<5	2.96	2	12	52	31	4.19	<1	0.30	<10	0.78	1342	8	0.02	3	1276	6	0.39	<5	4	186	<5	<0.01	<10	13	25	<10	151	2
8V2472RA/RJ	HL08-11	84104	121.16	123.16	2.00	0.11	<0.1	1.20	10	112	<0.5	<5	3.06	2	9	70	15	3.87	<1	0.23	<10	0.76	1228	4	0.02	3	896	3	0.39	<5	3	157	<5	<0.01	<10	<10	37	<10	214	2
8V2472RA/RJ	HL08-11	84105	123.16	127.50	4.34	0.08	<0.1	1.47	10	256	<0.5	<5	3.70	2	10	47	15	4.17	<1	0.20	<10	1.02	1563	3	0.02	3	1092	2	0.24	<5	4	209	<5	0.01	<10	11	44	<10	151	3
8V2472RA/RJ	HL08-11	84106	127.50	131.90	4.40	0.15	<0.1	1.52	26	210	<0.5	<5	3.68	2	11	49	33	4.28	<1	0.19	<10	0.88	1397	6	0.02	3	1151	3	0.53	<5	3	145	<5	0.02	<10	11	50	<10	135	3
8V2472RA/RJ	HL08-11	84107	131.90	132.80	0.90	0.04	0.1	0.88	16	299	<0.5	<5	3.48	2	9	51	22	3.72	<1	0.24	<10	0.89	1474	3	0.02	3	883	4	0.48	<5	4	259	<5	<0.01	<10	10	31	<10	146	2
8V2472RA/RJ	HL08-11	84108	132.80	140.00	7.20	0.06	0.1	1.38	7	140	<0.5	<5	3.07	1	9	69	19	3.60	<1	0.18	<10	0.82	1188	9	0.03	3	888	3	0.30	<5	4	100	<5	0.02	<10	10	44	<10	99	3
8V2472RA/RJ	HL08-11	84109	140.00	141.77	1.77	0.04	<0.1	1.32	17	97	<0.5	<5	3.14	1	8	52	11	3.55	<1	0.19	<10	0.79	1247	7	0.02	3	815	10	0.50	<5	3	114	<5	<0.01	<10	<10	41	<10	94	2
HL08-12 - Zone: 49er, Pad 17: 435084E, G223512N, Elev: 1212m, Az: 220, Dip: -55, EOH: 247.87m																																								
8V2472RA/RJ	HL08-12	84110	0.36	2.00	1.64	0.05	1.1	1.55	41	142	<0.5	<5	0.91	2	12	28	21	4.19	<1	0.24	10	0.80	1099	4	0.02	4	1098	15	1.11	<5	2	45	<5	0.01	<10	<10	29	<10	85	3
8V2472RA/RJ	HL08-12	84111	17.00	19.00	2.00	0.08	3.6	1.25	262	144	<0.5	<5	1.63	2	8	30	34	3.78	<1	0.34	<10	0.44	1281	14	0.01	3	1075	60	1.31	10	2	56	<5	<0.01	<10	16	23	<10	132	2
8V2472RA/RJ	HL08-12	8411																																						

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																										
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V2508RA/RJ	HL08-12	84153	125.00	126.00	1.00	0.63	6.0	1.98	65	52	0.9	<5	3.36	23	19	19	321	5.04	<1	0.21	<10	1.19	1954	5	0.02	2	982	2931	1.48	<5	48	<5	0.15	<10	<10	86	<10	2952	4	
8V2508RA/RJ	HL08-12	84154	126.00	127.50	1.50	0.71	3.6	1.41	49	39	0.7	<5	3.89	2	15	33	452	3.46	<1	0.21	<10	0.76	1361	15	0.01	2	793	38	0.82	<5	4	58	<5	0.11	<10	<10	64	<10	206	3
8V2508RA/RJ	HL08-12	84155	Std	PM1112		1.31	232.5	0.82	1655	86	<0.5	54	4.15	2	55	20	2263	2.89	2	0.08	10	0.23	817	122	0.05	22	776	355	0.58	308	1	134	<5	0.04	<10	<10	22	15	281	7
8V2508RA/RJ	HL08-12	84156	127.50	129.50	2.00	0.18	1.7	1.84	38	41	0.9	<5	3.95	2	17	13	322	4.15	<1	0.19	<10	1.13	1572	20	0.02	2	1035	17	0.55	<5	4	69	<5	0.14	<10	<10	80	<10	208	5
8V2508RA/RJ	HL08-12	84157	129.50	131.50	2.00	0.60	1.1	1.86	57	39	0.8	<5	2.82	2	19	25	298	3.87	<1	0.20	<10	1.17	1272	37	0.02	3	990	13	0.68	<5	4	66	<5	0.16	<10	<10	75	<10	212	4
8V2508RA/RJ	HL08-12	84158	131.50	132.94	1.44	0.79	1.7	2.03	30	49	0.9	<5	3.26	2	18	20	405	4.06	<1	0.18	<10	1.35	1175	15	0.02	3	1004	31	0.32	<5	6	65	<5	0.18	<10	<10	97	<10	234	6
8V2508RA/RJ	HL08-12	84159	132.94	134.94	1.06	0.40	1.9	1.94	16	29	0.7	<5	1.52	2	17	38	371	4.24	<1	0.10	<10	1.17	952	69	0.02	2	878	23	0.25	<5	4	87	<5	0.15	<10	<10	77	<10	212	3
8V3063RA/RJ	HL08-12	120360	134.00	135.00	1.00	0.31	0.6	2.35	<5	63	<0.5	<5	1.78	<1	21	23	164	4.58	<1	0.19	<10	1.65	1286	10	0.04	<1	1215	11	0.07	<5	5	49	<5	0.16	<10	<10	100	<10	265	3
8V3063RA/RJ	HL08-12	120361	135.00	136.00	1.00	0.50	0.3	1.81	15	47	<0.5	<5	2.75	1	17	30	19	3.34	<1	0.14	<10	1.12	1204	67	0.04	<1	1074	9	0.19	<5	3	78	<5	0.13	<10	<10	73	<10	188	6
8V3063RA/RJ	HL08-12	120362	136.00	137.00	1.00	0.46	13.0	1.89	13	51	<0.5	<5	2.31	1	20	18	22	3.83	<1	0.18	<10	1.23	1105	33	0.03	<1	1109	11	0.13	<5	4	72	<5	0.13	<10	<10	77	<10	229	3
8V3063RA/RJ	HL08-12	120363	137.00	138.00	1.00	1.02	1.6	2.07	75	55	<0.5	<5	2.96	2	18	16	138	4.78	<1	0.22	<10	1.26	1419	30	0.03	<1	1130	13	0.36	<5	4	59	<5	0.11	<10	<10	81	<10	289	3
8V3063RA/RJ	HL08-12	120364	138.00	139.00	1.00	0.43	0.6	2.08	17	72	<0.5	<5	2.62	1	19	14	43	4.51	<1	0.24	<10	1.34	1410	20	0.03	<1	1188	13	0.56	<5	5	61	<5	0.13	<10	<10	86	<10	266	3
8V2508RA/RJ	HL08-12	84160	139.00	141.00	2.00	0.34	1.0	2.20	16	69	1.0	<5	2.98	2	20	18	353	4.24	<1	0.22	<10	1.43	1306	26	0.03	1	1136	8	0.35	<5	5	109	<5	0.20	<10	<10	98	<10	229	5
8V2508RA/RJ	HL08-12	84161	141.00	142.61	1.61	0.29	2.6	1.73	103	76	0.9	<5	4.01	3	21	13	207	4.54	<1	0.35	<10	0.98	1676	19	0.01	1	1323	15	1.89	<5	4	86	<5	0.16	<10	<10	99	<10	280	3
8V2508RA/RJ	HL08-12	84162	142.61	143.09	0.48	0.16	1.9	0.50	132	46	<0.5	<5	7.71	7	10	68	59	2.34	<1	0.23	<10	0.21	1664	18	0.01	1	564	222	2.20	<5	2	293	<5	0.06	<10	<10	14	<10	718	1
8V2508RA/RJ	HL08-12	84163	143.09	145.00	1.91	0.43	2.1	1.96	17	64	1.0	<5	4.45	2	20	8	270	4.25	<1	0.21	<10	1.21	1659	19	0.02	1	1339	12	2.27	<5	5	114	<5	0.16	<10	<10	87	<10	279	5
8V2508RA/RJ	HL08-12	84164	145.00	146.42	1.42	0.94	3.2	2.07	29	73	0.9	<5	2.49	2	22	12	351	4.88	<1	0.27	<10	1.26	1723	24	0.01	1	1400	16	0.65	<5	4	54	<5	0.15	<10	<10	73	<10	379	3
8V2508RA/RJ	HL08-12	84165	146.42	146.94	0.52	4.98	6.0	0.58	507	46	<0.5	<5	5.57	13	14	105	171	3.65	<1	0.19	<10	0.24	1083	30	0.01	2	618	65	3.37	<5	2	219	<5	0.07	<10	<10	17	<10	626	2
8V2508RA/RJ	HL08-12	84166	146.94	148.00	1.06	0.84	2.5	2.12	22	54	1.0	<5	4.43	1	22	12	302	4.74	<1	0.16	<10	1.43	1901	42	0.02	<1	1264	10	0.47	<5	5	102	<5	0.18	<10	<10	95	<10	284	4
8V2508RA/RJ	HL08-12	84167	148.00	150.00	2.00	0.28	1.4	2.02	14	50	0.9	<5	4.48	1	15	25	157	3.35	<1	0.10	<10	1.27	1357	79	0.02	<1	1202	6	0.12	<5	3	93	<5	0.14	<10	<10	66	<10	192	10
8V2508RA/RJ	HL08-12	84168	150.00	152.00	2.00	0.46	1.4	1.78	15	52	1.0	<5	4.23	1	19	10	156	3.97	<1	0.16	<10	1.15	1537	62	0.02	<1	1272	11	0.33	<5	4	87	<5	0.16	<10	<10	87	<10	179	4
8V2508RA/RJ	HL08-12	84169	152.00	154.00	2.00	0.85	2.4	1.80	29	53	0.8	<5	4.28	1	20	11	224	4.40	<1	0.22	<10	1.06	1704	25	0.01	1	1309	11	0.66	<5	4	77	<5	0.12	<10	<10	70	<10	251	3
8V2508RA/RJ	HL08-12	84170	154.00	156.00	2.00	0.45	1.9	1.56	122	50	0.7	<5	4.30	3	19	11	121	4.54	<1	0.23	<10	0.83	1695	25	0.02	<1	1276	36	1.50	<5	4	62	<5	0.11	<10	<10	68	<10	252	3
8V2508RA/RJ	HL08-12	84171	156.00	158.00	2.00	0.53	1.5	2.03	25	47	0.8	<5	4.29	1	22	8	134	4.85	<1	0.21	<10	1.26	1596	30	0.02	1	1414	10	0.44	<5	4	66	<5	0.13	<10	<10	82	<10	255	3
8V2508RA/RJ	HL08-12	84172	158.00	159.40	1.40	1.10	1.8	2.11	20	50	0.8	<5	3.15	1	22	12	139	4.89	<1	0.21	<10	1.28	1269	60	0.02	<1	1345	15	0.51	<5	4	65	<5	0.13	<10	<10	80	<10	273	3
8V2508RA/RJ	HL08-12	84173	159.40	160.83	1.43	0.81	3.0	1.71	17	46	0.6	<5	5.42	1	19	12	388	4.16	<1	0.17	<10	1.02	1625	79	0.02	1	1285	11	0.50	<5	4	85	<5	0.11	<10	<10	70	<10	210	3
8V2508RA/RJ	HL08-12	84174	160.83	162.50	1.67	0.89	1.6	1.76	<5	117	<0.5	<5	5.08	1	17	10	344	4.12	<1	0.16	<10	1.05	1666	48	0.02	<1	1259	6	0.22	<5	4	189	<5	0.05	<10	<10	71	<10	252	3
8V2508RA/RJ	HL08-12	84175	162.50	164.50	2.00	0.62	2.2	1.86	6	58	<0.5	<5	5.52	1	17	13	411	4.22	<1	0.18	<10	1.15	1740	57	0.02	<1	1264	12	0.29	<5	4	106	<5	0.05	<10	<10	72	<10	253	2
8V2508RA/RJ	HL08-12	84176	164.50	165.30	0.80	0.78	1.2	1.97	<5	72	0.8	<5	3.71	1	21	9	164	4.52	<1	0.19	<10	1.26	1352	47	0.02	1	1377	10	0.25	<5	5	102	<5	0.14	<10	<10	87	<10	313	3
8V2508RA/RJ	HL08-12	84177	165.30	167.30	2.00	0.57	2.4	2.07	46	63	0.9	<5	3.91	2	21	7	319	4.91	<1	0.22	<10	1.31	1368	50	0.02	<1	1361	13	0.86	<5	5	66	<5	0.16	<10	<10	87	<10		

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																											
					0.5-1.0	1.0-3.0	3.0-5.0	>5.0	5-10	10-50	50-100	>100	2500-5000	5000-10000	>10000	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm													
8V2508RA/RJ	HL08-12	84220	222.50	224.00	1.50	0.26	0.6	1.43	43	84	<0.5	<5	7.43	3	11	13	109	3.82	<1	0.27	12	0.59	3201	9	0.01	2	1092	90	0.47	<5	3	139	<5	0.03	<10	<10	65	<10	278	2
8V2508RA/RJ	HL08-12	84221	224.00	225.78	1.78	0.31	0.6	1.41	38	102	0.5	<5	5.55	2	12	17	269	3.56	<1	0.32	11	0.60	2572	7	0.01	2	1131	9	0.56	<5	3	117	<5	0.06	<10	<10	58	<10	173	3
8V2508RA/RJ	HL08-12	84222	225.78	227.56	1.78	0.80	6.1	0.76	199	36	<0.5	<5	>15.00	17	7	19	386	3.43	<1	0.13	12	0.45	5214	8	0.01	2	359	1567	2.26	<5	1	174	<5	0.02	<10	<10	25	<10	1794	2
8V2508RA/RJ	HL08-12	84223	227.56	229.50	1.94	0.22	8.7	1.28	115	92	<0.5	<5	6.67	47	13	19	468	4.78	1	0.24	<10	0.67	2923	21	0.01	3	796	1405	2.73	<5	2	116	<5	0.03	<10	<10	47	<10	4903	3
8V2508RA/RJ	HL08-12	84224	229.50	231.50	2.00	0.16	1.4	1.62	67	142	0.6	<5	2.71	5	13	14	149	4.06	1	0.36	<10	0.73	1769	22	0.01	3	1169	48	0.81	<5	3	85	<5	0.08	<10	<10	53	<10	523	3
8V2508RA/RJ	HL08-12	84225	Blank	Blank	0.01	<0.2	0.94	<5	213	0.5	<5	0.50	1	7	88	<1	1.89	<1	0.47	<10	0.56	529	<2	0.06	5	626	5	0.01	<5	2	57	<5	0.12	<10	<10	37	<10	62	2	
8V2508RA/RJ	HL08-12	84226	231.50	233.50	2.00	0.23	3.5	1.67	130	108	<0.5	<5	2.62	16	15	26	175	5.30	<1	0.30	<10	0.85	1822	24	0.01	4	1048	428	2.04	<5	3	80	<5	0.05	<10	<10	62	<10	1750	3
8V2508RA/RJ	HL08-12	84227	233.50	234.50	1.00	0.15	8.5	1.90	109	85	<0.5	<5	4.51	79	15	20	314	6.11	1	0.21	<10	1.10	2561	11	0.01	5	976	806	2.55	6	3	109	<5	0.04	<10	<10	70	<10	8855	4
8V2508RA/RJ	HL08-12	84228	234.50	235.50	1.00	0.22	4.7	1.40	99	94	<0.5	<5	3.97	39	10	24	120	4.29	1	0.28	<10	0.71	2142	12	0.01	3	942	1486	1.76	<5	2	96	<5	0.03	<10	<10	47	<10	4334	3
8V2508RA/RJ	HL08-12	84229	235.50	237.50	2.00	0.25	3.5	2.40	116	104	0.5	<5	5.11	5	21	21	226	7.32	1	0.35	<10	1.24	3047	47	0.01	4	1264	347	1.98	5	3	106	<5	0.05	<10	<10	83	<10	530	4
8V2508RA/RJ	HL08-12	84230	237.50	239.50	2.00	0.29	2.1	1.53	109	102	<0.5	<5	4.54	3	12	20	156	4.15	<1	0.30	<10	0.69	2236	29	0.01	3	1060	128	0.80	<5	2	107	<5	0.04	<10	<10	50	<10	270	3
8V2508RA/RJ	HL08-12	84231	239.50	241.50	2.00	0.24	1.2	1.50	41	109	0.5	<5	3.71	2	12	10	119	3.54	<1	0.34	12	0.68	1878	17	0.01	3	1150	76	0.33	<5	3	110	<5	0.03	<10	<10	44	<10	239	2
8V2508RA/RJ	HL08-12	84232	241.50	243.50	2.00	0.15	1.3	1.69	68	134	<0.5	<5	2.77	5	13	21	130	4.71	<1	0.32	10	0.94	1972	11	0.01	3	1039	50	0.73	<5	3	80	<5	<0.01	<10	<10	53	<10	529	3
8V2508RA/RJ	HL08-12	84233	243.50	244.75	1.25	0.24	1.6	1.96	32	138	<0.5	<5	1.64	1	16	14	141	4.64	<1	0.36	<10	0.97	1937	18	0.01	2	1350	13	0.83	<5	3	65	<5	0.01	<10	<10	54	<10	196	2
8V2508RA/RJ	HL08-12	84234	244.75	246.00	1.25	0.05	2.0	1.98	43	97	<0.5	<5	3.67	15	12	28	213	5.33	<1	0.19	<10	0.92	1888	12	0.01	1	974	343	1.02	<5	4	112	<5	0.01	<10	<10	58	20	1738	2
8V2508RA/RJ	HL08-12	84235	246.00	247.87	1.87	0.31	3.7	1.79	49	98	0.5	<5	2.33	3	16	9	254	4.48	<1	0.33	<10	0.86	1599	24	0.01	2	1415	376	0.64	<5	3	66	<5	0.02	<10	<10	57	<10	426	2
HL08-13 - Zone: Yellowstone, Pad 18: 435049,6223582N, Elev: 1211m, Az: 340, Dip: -45, EOH: 96.65m																																								
8V2558RA/RJ	HL08-13	84295	2.09	4.95	2.86	0.09	3.5	1.79	129	161	<0.5	<5	0.30	4	21	39	84	5.28	<1	0.29	<10	0.91	2029	3	0.02	2	1160	70	1.54	9	4	2	6	>10.00	<10	<10	83	<10	225	3
8V2558RA/RJ	HL08-13	84296	8.00	10.00	2.00	0.40	6.1	1.87	226	109	<0.5	<5	1.12	4	28	24	87	5.97	<1	0.37	<10	0.85	2519	<2	0.01	3	1146	84	2.67	4	4	3	5	>10.00	<10	13	53	<10	266	3
8V2558RA/RJ	HL08-13	84297	10.00	11.00	1.00	1.44	12.2	1.66	215	112	<0.5	<5	1.62	5	25	24	82	6.16	<1	0.33	<10	0.87	2713	<2	0.01	3	1122	421	2.99	7	4	65	<5	>10.00	<10	18	62	<10	500	3
8V2558RA/RJ	HL08-13	84298	11.00	13.00	2.00	1.52	17.5	2.21	110	181	<0.5	<5	0.72	4	23	12	73	5.77	<1	0.28	<10	1.34	2714	<2	0.01	3	1231	319	1.30	6	4	41	<5	>10.00	<10	13	92	<10	368	3
8V2558RA/RJ	HL08-13	84299	13.00	15.00	2.00	0.08	8.2	2.52	88	288	<0.5	<5	0.34	3	23	13	55	6.20	<1	0.32	11	1.43	2583	5	0.01	3	1325	59	1.02	8	5	10	<5	>10.00	<10	11	111	<10	291	4
8V2558RA/RJ	HL08-13	84300	Blank	Blank	0.03	<0.1	1.13	<5	268	0.5	<5	0.54	1	7	116	<1	2.38	<1	0.57	<10	0.69	662	2	0.07	6	702	11	0.02	<5	3	51	6	>10.00	<10	<10	44	<10	59	3	
8V2558RA/RJ	HL08-13	84301	15.00	16.70	1.70	0.12	5.5	1.96	146	145	<0.5	<5	1.41	2	19	24	44	5.20	<1	0.36	<10	1.10	2432	6	0.01	2	1135	140	1.33	7	4	47	<5	>10.00	<10	<10	85	<10	127	3
8V2558RA/RJ	HL08-13	84302	16.70	17.30	0.60	0.68	115.0	0.45	705	99	<0.5	<5	3.41	10	12	112	67	4.09	<1	0.19	<10	0.19	1854	7	0.01	4	436	661	3.98	26	2	90	<5	>10.00	<10	10	24	<10	1196	2
8V2558RA/RJ	HL08-13	84303	17.30	19.00	1.70	0.13	2.1	2.71	90	101	<0.5	<5	2.48	2	25	11	66	5.92	<1	0.30	<10	1.70	3181	<2	0.01	5	996	54	1.18	6	9	90	5	>10.00	<10	16	104	<10	112	4
8V2558RA/RJ	HL08-13	84304	19.00	21.00	2.00	0.33	38.1	2.80	85	129	<0.5	<5	2.03	5	20	16	211	5.90	<1	0.20	<10	2.01	3311	3	0.01	4	973	395	1.10	10	6	49	5	>10.00	<10	17	158	<10	466	4
8V2558RA/RJ	HL08-13	84305	21.00	23.00	2.00	0.19	27.5	2.73	219	131	<0.5	<5	1.47	6	20	14	167	5.94	<1	0.19	<10	1.96	2895	2	0.01	5	943	363	1.33	8	7	41	5	>10.00	<10	13	172	<10	550	4
8V2558RA/RJ	HL08-13	84306	23.00	25.00	2.00	0.24	11.5	2.79	220	112	<0.5	<5	2.31	3	25	8	226	6.43	<1	0.14	<10	1.89	3286	<2	0.02	4	1134	61	1.33	6	8	81	5	>10.00	<10	17	224	<10	241	4
8V2558RA/RJ	HL08-13	84307	25.00	27.00	2.00	0.20	2.3	2.62	124	138	<0.5	<5	2.08	3	24	5	98	6.64	<1	0.23	<10	1.84	2823	<2	0.01	5	1195	19	1.32	5	7	54	<5	>10.00	<10	17	208	<10	139	4
8V2558RA/RJ	HL08-13	84308	27.00	29.00	2.00	0.11	2.6	2.57	93	153	<0.5	<5	1.65	3	20	24	87	6.39	<1	0.24	<10	1.92	2792	<2	0.01	5	1146	16	1.74	7	7	43	<5	0.01	<10	20	189	<10	174	4
8V2558RA/RJ	HL08-13	84309	29.00	31.00	2.00</																																			

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																										
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
						0.5-1.0	1.0-3.0	3.0-5.0	>5.0	5-10	10-50	50-100	>100																											
8V2558RA/RJ	HL08-14	84238	3.83	5.83	2.00	0.32	4.1	1.90	161	142	<0.5	<5	1.28	3	27	20	46	6.39	<1	0.39	<10	0.82	2291	2	0.01	4	1440	65	2.51	8	4	66	<5	0.01	<10	18	83	<10	166	4
8V2558RA/RJ	HL08-14	84239	5.83	7.83	2.00	0.48	4.6	2.11	106	175	<0.5	<5	1.16	5	21	35	172	5.88	<1	0.41	<10	1.04	2534	<2	0.01	6	1242	120	1.64	6	4	71	<5	0.01	<10	16	77	<10	458	3
8V2558RA/RJ	HL08-14	84240	7.83	9.83	2.00	0.09	2.4	2.27	98	132	<0.5	<5	0.61	2	23	16	70	5.98	<1	0.30	<10	1.24	2486	<2	0.02	6	1351	26	1.22	5	4	55	<5	0.01	<10	20	69	<10	109	3
8V2558RA/RJ	HL08-14	84241	9.83	11.00	1.17	0.32	5.9	2.05	140	179	<0.5	<5	0.73	3	23	21	202	5.69	<1	0.37	10	1.01	2635	<2	0.01	7	1205	48	1.32	7	3	99	<5	0.01	<10	18	69	<10	150	3
8V2558RA/RJ	HL08-14	84242	11.00	13.00	2.00	0.23	10.6	2.22	157	167	<0.5	<5	0.51	3	22	14	104	6.09	<1	0.36	11	1.22	2102	<2	0.01	8	1038	118	1.58	9	3	46	<5	0.01	<10	17	66	<10	221	3
8V2558RA/RJ	HL08-14	84243	13.00	15.00	2.00	0.08	4.5	2.83	119	290	<0.5	<5	0.63	4	24	18	154	6.62	<1	0.39	<10	1.83	2312	2	0.01	6	1297	110	0.97	7	5	58	<5	<0.01	<10	21	101	<10	306	4
8V2558RA/RJ	HL08-14	84244	15.00	17.00	2.00	0.22	16.9	1.82	375	131	<0.5	<5	1.98	34	20	22	165	5.70	<1	0.32	<10	1.12	2156	3	0.01	5	1043	180	1.85	9	3	109	<5	<0.01	<10	20	61	<10	3169	3
8V2558RA/RJ	HL08-14	84245	17.00	19.00	2.00	0.35	5.5	1.98	228	128	<0.5	<5	1.58	6	21	40	82	6.85	<1	0.31	<10	1.21	2190	3	0.01	5	939	392	3.22	9	4	108	<5	0.01	<10	22	88	<10	438	4
8V2558RA/RJ	HL08-14	84246	19.00	20.00	1.00	0.47	5.8	2.12	1085	117	<0.5	<5	0.59	42	22	34	125	7.27	<1	0.29	<10	1.40	1916	2	0.01	4	1065	417	3.39	9	4	45	<5	0.01	<10	20	103	<10	3636	4
8V2558RA/RJ	HL08-14	84247	20.00	21.00	1.00	0.21	4.4	2.50	429	105	<0.5	<5	0.86	14	24	19	95	7.50	<1	0.24	<10	1.64	2309	3	0.01	6	1129	210	2.83	8	5	55	<5	0.01	<10	24	130	<10	1178	4
8V2558RA/RJ	HL08-14	84248	21.00	22.00	1.00	0.28	6.0	1.54	154	114	<0.5	<5	1.71	3	18	64	179	4.95	<1	0.32	<10	0.75	2279	4	0.01	7	844	313	2.65	6	3	119	6	0.01	<10	12	43	<10	208	3
8V2558RA/RJ	HL08-14	84249	22.00	23.00	1.00	0.19	2.4	1.62	107	116	<0.5	<5	1.76	2	19	23	53	5.37	<1	0.23	<10	1.05	2339	<2	0.01	4	939	115	2.56	5	4	115	6	0.01	<10	12	83	<10	153	3
8V2558RA/RJ	HL08-14	84250	23.00	24.00	1.00	0.39	4.9	2.24	179	117	<0.5	<5	1.06	3	22	26	103	6.34	<1	0.30	<10	1.57	2530	2	0.01	4	1015	234	2.69	5	4	37	5	0.01	<10	14	91	<10	257	4
8V2558RA/RJ	HL08-14	84251	24.00	24.93	0.93	0.36	4.4	2.61	47	145	<0.5	<5	1.46	7	19	28	76	5.43	<1	0.28	<10	1.98	2823	<2	0.01	4	1142	948	0.90	5	6	55	<5	0.01	<10	14	124	<10	742	3
8V2558RA/RJ	HL08-14	84252	24.93	26.00	1.07	0.15	1.9	2.86	39	133	<0.5	<5	1.97	4	23	11	99	6.41	<1	0.27	<10	2.00	3235	<2	0.01	4	1223	67	1.70	5	6	85	5	0.01	<10	19	145	<10	268	4
8V2558RA/RJ	HL08-14	84253	26.00	27.12	1.12	0.17	9.9	2.52	59	150	<0.5	<5	0.74	43	20	16	276	6.01	<1	0.28	<10	1.87	2517	<2	0.01	4	1097	862	1.90	9	4	26	5	0.01	<10	13	125	<10	4144	4
8V2558RA/RJ	HL08-14	84254	27.12	28.00	0.88	0.25	6.3	1.69	156	115	<0.5	<5	2.03	8	16	29	42	5.81	<1	0.20	<10	1.21	2326	2	0.01	3	830	618	3.50	6	4	54	5	0.01	<10	14	115	<10	802	4
8V2558RA/RJ	HL08-14	84255	28.00	29.00	1.00	0.17	8.1	1.41	156	136	<0.5	<5	0.90	3	20	71	46	5.07	<1	0.36	<10	0.71	1635	6	0.01	4	1052	1465	3.19	8	3	33	<5	<0.01	<10	<10	64	<10	243	3
8V2558RA/RJ	HL08-14	84256	Blank	Blank	Blank	<0.01	<0.1	1.07	<5	245	<0.5	<5	0.51	<1	6	108	<1	2.14	<1	0.53	<10	0.62	596	<2	0.07	6	707	8	<0.01	<5	2	44	10	0.13	21	<10	41	<10	54	2
8V2558RA/RJ	HL08-14	84257	29.00	30.00	1.00	0.20	5.1	2.15	180	85	<0.5	<5	1.30	4	21	28	19	7.45	<1	0.30	<10	1.31	3067	6	0.01	4	1045	189	>5.00	7	4	53	7	0.01	<10	23	86	<10	228	5
8V2558RA/RJ	HL08-14	84258	30.00	31.00	1.00	0.29	12.5	1.99	182	99	<0.5	<5	0.68	6	23	29	19	7.35	<1	0.23	<10	1.33	3192	<2	0.01	4	1158	322	4.36	6	4	25	5	0.01	<10	21	91	<10	511	4
8V2558RA/RJ	HL08-14	84259	31.00	32.00	1.00	0.28	4.5	0.97	205	106	<0.5	<5	2.13	5	18	100	21	5.67	<1	0.21	<10	0.56	2305	3	0.01	5	936	285	4.56	7	3	101	<5	0.01	<10	16	55	<10	389	3
8V2558RA/RJ	HL08-14	84260	32.00	33.00	1.00	0.44	7.0	1.08	274	69	<0.5	<5	0.75	13	22	40	43	6.79	<1	0.22	<10	0.66	1931	3	0.01	4	919	609	>5.00	9	4	40	<5	0.01	<10	24	97	<10	812	4
8V2558RA/RJ	HL08-14	84261	33.00	34.00	1.00	0.27	4.1	0.96	219	100	<0.5	<5	1.74	4	17	81	<1	5.75	<1	0.25	<10	0.60	2039	2	0.01	5	1008	288	4.15	7	3	166	<5	0.01	<10	24	58	<10	337	4
8V2558RA/RJ	HL08-14	84262	34.00	35.00	1.00	0.21	3.1	0.24	79	123	<0.5	<5	1.13	10	6	96	<1	3.19	<1	0.20	<10	0.09	619	<2	0.01	3	288	342	2.61	<5	1	53	<5	<0.01	<10	12	12	<10	1311	2
8V2558RA/RJ	HL08-14	84263	35.00	36.00	1.00	0.13	6.1	0.29	107	172	<0.5	<5	4.33	12	5	121	21	1.96	<1	0.20	<10	1.10	1957	<2	0.01	3	303	647	1.62	8	1	236	<5	<0.01	<10	17	13	<10	1521	2
8V2558RA/RJ	HL08-14	84264	36.00	37.00	1.00	0.87	5.2	0.42	154	122	<0.5	<5	2.20	9	4	127	<1	2.82	<1	0.18	<10	0.26	1401	<2	0.01	4	326	435	1.55	9	1	102	<5	<0.01	<10	18	13	<10	1027	2
8V2558RA/RJ	HL08-14	84265	37.00	38.00	1.00	0.40	10.3	0.30	395	67	<0.5	<5	1.12	14	6	122	6	5.24	<1	0.23	<10	0.11	658	5	0.01	3	382	1670	>5.00	11	1	73	<5	<0.01	<10	20	8	<10	2043	3
8V2558RA/RJ	HL08-14	84266	38.00	39.00	1.00	0.59	12.9	0.21	410	75	<0.5	<5	2.21	9	4	251	14	3.65	<1	0.15	<10	0.06	1230	5	0.01	7	254	707	3.51	18	1	168	<5	<0.01	<10	15	5	<10	1086	2
8V2558RA/RJ	HL08-14	84267	39.00	40.00	1.00	0.74	15.2	0.59	602	47	<0.5	<5	1.09	12	7	130	5	8.11	<1	0.20	<10	0.32	1088	2	0.02	4	463	889	>5.00	41	1	97	<5	<0.01	<10	32	17	<10	1278	5
8V2558RA/R																																								

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0					Ag: 5-10 10-50 50-100 >100					Pb/Zn: 2500-5000 5000-10000 >10000																										
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm	
8V3672RA/RJ	HL08-15	122655	33.38	33.50	0.12	1.29	6.8	0.95	813	156	<0.5	9	4.31	22	15	26	133	3.89	<1	0.55	<10	0.88	2150	32	0.02	2	1178	364	0.87	<5	3	232	<5	<0.01	<10	<10	<10	21	<10	131	2
8V2558RA/RJ	HL08-15	84359	33.50	34.80	1.30	0.36	5.6	0.51	73	96	<0.5	<5	5.59	3	14	22	119	4.54	<1	0.33	<10	1.10	2606	15	0.02	2	1111	34	0.92	5	3	312	<5	<0.01	<10	16	16	<10	122	2	
8V2558RA/RJ	HL08-15	84360	34.80	36.60	1.80	0.20	2.6	0.79	59	113	<0.5	<5	3.93	2	15	15	81	4.32	<1	0.36	<10	0.92	1978	17	0.02	2	1361	15	0.92	<5	4	211	<5	<0.01	<10	10	18	<10	91	2	
8V2558RA/RJ	HL08-15	84361	36.60	38.30	1.70	0.38	0.6	1.00	54	207	<0.5	<5	3.88	1	18	20	62	4.27	<1	0.36	<10	0.93	2021	33	0.02	2	1361	11	0.85	<5	3	200	<5	<0.01	<10	10	27	<10	81	3	
8V3672RA/RJ	HL08-15	122656	38.30	40.43	2.13	0.22	1.2	1.82	84	143	<0.5	<5	3.61	3	20	13	16	4.73	<1	0.39	<10	1.17	2028	50	0.03	2	1489	35	0.60	<5	3	130	<5	<0.01	<10	<10	51	<10	106	2	
8V2558RA/RJ	HL08-15	84362	40.88	42.00	1.12	0.11	1.2	1.32	97	122	<0.5	<5	2.27	1	19	30	43	4.10	<1	0.30	<10	0.76	1520	11	0.01	2	1096	47	1.27	<5	2	76	<5	<0.01	<10	<10	33	<10	111	2	
8V2558RA/RJ	HL08-15	84363	42.00	43.05	0.34	0.34	3.2	1.55	263	132	<0.5	<5	3.20	4	19	16	96	4.55	<1	0.34	<10	0.83	1728	9	0.01	3	1223	88	1.10	7	2	100	<5	<0.01	<10	13	36	<10	389	2	
8V2558RA/RJ	HL08-15	84364	43.05	45.00	1.95	0.44	6.6	1.65	152	137	<0.5	<5	3.94	5	15	17	187	4.95	<1	0.36	<10	0.85	1961	16	0.01	1	1304	185	1.69	<5	3	127	<5	<0.01	<10	17	49	<10	435	3	
8V2558RA/RJ	HL08-15	84365	45.00	46.65	1.65	0.58	4.4	1.88	31	168	<0.5	<5	4.23	3	18	14	225	5.10	<1	0.36	<10	0.83	2011	33	0.01	1	1208	92	0.81	<5	3	122	<5	0.01	<10	18	55	<10	293	3	
8V2558RA/RJ	HL08-15	84366	46.65	47.40	0.75	0.15	2.3	2.01	38	174	<0.5	<5	5.51	3	19	5	297	5.37	<1	0.38	<10	1.01	2332	27	0.01	2	1491	27	0.88	<5	4	217	<5	0.01	<10	22	65	<10	208	3	
8V2558RA/RJ	HL08-15	84367	47.40	49.30	1.90	0.20	2.1	2.15	30	180	<0.5	<5	5.74	4	16	1	298	5.82	<1	0.38	<10	1.09	2408	34	0.02	1	1489	19	0.92	<5	4	251	<5	0.01	<10	20	69	<10	248	3	
8V2558RA/RJ	HL08-15	84368	49.30	50.40	1.10	0.07	2.4	1.35	220	186	<0.5	<5	6.53	4	19	6	179	4.24	<1	0.35	<10	0.80	2650	23	0.01	2	1340	51	1.48	<5	3	261	<5	0.01	<10	18	39	<10	212	3	
8V2558RA/RJ	HL08-15	84369	50.40	52.00	1.60	0.22	2.4	1.78	61	135	<0.5	<5	4.74	4	17	7	196	5.17	<1	0.38	<10	0.91	2344	43	0.01	1	1291	51	1.36	<5	3	138	<5	<0.01	<10	19	58	<10	276	3	
8V2558RA/RJ	HL08-15	84370	52.00	53.65	1.65	0.12	2.3	1.88	30	133	<0.5	<5	6.05	3	18	6	198	5.33	<1	0.35	<10	0.96	2394	34	0.02	2	1234	14	1.02	<5	4	327	<5	<0.01	<10	23	56	<10	184	3	
8V2558RA/RJ	HL08-15	84371	53.65	54.55	0.90	2.89	32.8	1.04	128	103	<0.5	<5	4.19	13	16	21	184	5.44	<1	0.31	<10	0.78	1993	35	0.01	2	1211	388	3.34	<5	3	294	<5	<0.01	<10	21	32	<10	1560	3	
8V2936RA/RJ	HL08-15	120040	54.55	55.55	1.00	0.11	0.8	0.44	191	68	<0.5	<5	3.60	3	13	122	21	3.24	<1	0.27	<10	0.43	1228	4	0.01	4	904	17	1.97	<5	2	79	<5	<0.01	<10	<10	12	<10	64	2	
8V2936RA/RJ	HL08-15	120041	55.55	56.37	0.82	0.18	2.3	1.84	34	167	<0.5	<5	5.73	2	20	27	162	5.88	<1	0.36	<10	1.18	2736	8	0.01	1	1573	13	1.41	<5	5	160	<5	<0.01	<10	<10	73	<10	271	2	
8V2936RA/RJ	HL08-15	120042	56.37	57.29	0.92	0.17	3.5	2.05	21	173	<0.5	<5	5.52	1	23	16	233	6.33	<1	0.35	<10	1.40	2715	13	0.01	1	1590	14	0.90	<5	4	183	<5	<0.01	<10	<10	73	<10	278	3	
8V2936RA/RJ	HL08-15	120043	57.29	58.59	1.30	0.15	2.7	1.43	53	167	<0.5	<5	3.30	2	16	18	208	5.67	<1	0.33	<10	0.78	1890	6	0.01	1	1489	14	0.99	<5	3	78	<5	<0.01	<10	<10	40	<10	260	2	
8V2936RA/RJ	HL08-15	120044	58.59	59.72	1.13	0.22	3.6	1.26	79	115	<0.5	<5	5.54	2	19	16	278	5.35	<1	0.31	<10	0.91	2199	66	0.01	1	1456	16	2.38	<5	3	147	<5	<0.01	<10	<10	41	<10	239	2	
8V2936RA/RJ	HL08-15	120045	59.72	61.15	1.43	0.18	3.9	1.84	22	143	<0.5	<5	4.02	1	20	19	381	5.43	<1	0.35	<10	1.07	2123	64	0.01	1	1438	19	0.91	<5	3	113	<5	<0.01	<10	<10	61	<10	282	2	
8V2558RA/RJ	HL08-15	84372	61.15	62.14	0.99	2.72	22.1	1.40	46	213	<0.5	<5	4.68	16	19	6	361	5.23	<1	0.44	<10	0.47	2052	26	0.01	1	1447	1185	0.84	<5	3	96	<5	<0.01	<10	16	30	<10	1879	3	
8V2558RA/RJ	HL08-15	84373	62.60	64.60	2.00	0.10	6.0	1.48	36	138	<0.5	<5	5.75	1	19	16	538	4.83	<1	0.37	<10	1.04	2394	86	0.01	1	1551	21	0.72	<5	4	260	<5	<0.01	<10	<10	34	<10	213	2	
8V2558RA/RJ	HL08-15	84374	64.60	66.60	2.00	0.35	2.4	0.92	38	114	<0.5	<5	3.87	1	15	16	194	3.99	<1	0.32	<10	0.83	1820	19	0.01	1	1671	26	0.62	<5	3	207	<5	<0.01	<10	<10	19	<10	211	2	
8V2596RA/RJ	HL08-15	84375	Std	PM11.16	0.10	744.1	0.80	586	200	<0.5	114	0.61	17	8	175	699	2.40	6	0.26	<10	0.57	337	578	0.06	6	628	937	1.29	1461	2	83	<5	0.06	<10	<10	29	<10	1004	3		
8V2596RA/RJ	HL08-15	84376	66.60	68.20	1.60	0.41	1.4	1.21	11	112	<0.5	<5	3.68	<1	13	19	79	3.94	<1	0.29	<10	0.94	1613	15	0.02	1	1599	13	0.19	<5	3	183	<5	<0.01	<10	<10	34	<10	209	2	
8V2596RA/RJ	HL08-15	84377	68.20	69.85	1.65	0.46	3.2	1.01	43	116	<0.5	<5	4.42	1	13	19	107	4.04	<1	0.32	<10	1.00	1865	22	0.02	1	1599	15	0.33	<5	3	291	<5	<0.01	<10	<10	24	<10	214	2	
8V2596RA/RJ	HL08-15	84378	69.85	70.90	1.05	0.54	2.0	1.37	20	72	<0.5	<5	4.76	<1	12	36	244	3.83	<1	0.21	<10	0.80	1739	18	0.02	1	1569	15	0.26	<5	3	267	<5	<0.01	<10	<10	45	<10	206	2	
8V2596RA/RJ	HL08-15	84379	70.90	73.15	2.25	0.33	2.5	1.01	109	130	<0.5	<5	3.43	2	14	23	170	4.43	<1	0.28	<10	0.59	1931	20	0.01	1	1654	16	0.66	<5	3	78	<5	<0.01	<10	<10	25	<10	216	2	
8V2596RA/RJ	HL08-15	84380	73.15	75.15	2.00	0.48	1.3	1.67	27	90	<0.5	<5	3.31	1	14	17	149	4.23	<1	0.28	<10	0.97	1631	14	0.02	<1	1681	64	0.50	<5	3	107	<5	0.01							

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																										
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V2690RA/RJ	HL08-16	84422	62.00	63.10	1.10	0.01	<0.1	2.61	130	52	0.7	<5	9.43	2	24	42	74	5.36	1	0.12	<10	2.14	2761	<2	0.01	13	1196	38	0.66	<5	14	202	<5	0.09	<10	<10	185	<10	170	4
8V2690RA/RJ	HL08-16	84423	63.10	64.00	0.90	0.02	<0.1	2.39	133	65	0.5	<5	10.69	3	21	37	80	5.13	1	0.10	<10	2.01	3087	<2	0.01	12	1189	4	0.74	<5	14	170	<5	0.07	<10	<10	189	<10	197	4
8V2690RA/RJ	HL08-16	84424	64.00	66.00	2.00	0.01	0.2	3.18	81	46	<0.5	<5	7.27	2	30	43	104	7.37	1	0.14	<10	2.61	3153	<2	0.02	17	1518	13	1.49	6	14	171	<5	0.02	<10	<10	227	<10	52	5
8V2690RA/RJ	HL08-16	84425	Std	PM 197		0.45	0.3	1.09	6756	21	<0.5	19	6.43	1	197	12	78	4.13	<1	0.05	13	0.26	767	16	0.09	35	1254	11	1.39	5	1	101	<5	0.05	<10	<10	43	<10	87	11
8V2690RA/RJ	HL08-16	84426	66.00	67.00	1.00	0.02	<0.1	2.18	72	46	<0.5	<5	7.48	1	27	38	65	4.73	1	0.18	<10	1.64	2773	<2	0.01	14	1321	2	0.61	<5	10	140	<5	0.03	<10	<10	146	<10	43	3
8V2690RA/RJ	HL08-16	84427	67.00	68.00	1.00	0.01	0.2	2.42	62	47	0.5	<5	8.54	1	28	36	82	5.78	1	0.19	<10	1.80	2831	<2	0.01	14	1402	6	1.25	5	10	158	<5	0.05	<10	<10	166	<10	32	4
8V2690RA/RJ	HL08-16	84428	68.00	70.00	2.00	0.02	<0.1	2.27	73	59	<0.5	<5	6.60	2	27	34	82	5.86	<1	0.19	<10	2.17	2786	<2	0.01	15	1363	13	1.12	5	10	152	<5	0.02	<10	<10	151	<10	81	4
8V2690RA/RJ	HL08-16	84429	70.00	71.40	1.40	0.01	0.2	2.94	112	60	0.5	<5	6.51	2	31	39	92	6.30	1	0.19	<10	2.39	3013	<2	0.01	16	1377	28	1.30	<5	11	148	<5	0.08	<10	<10	175	<10	87	4
8V2690RA/RJ	HL08-16	84430	71.40	72.90	1.40	0.01	<0.1	2.15	92	54	0.6	<5	7.51	2	30	35	65	6.69	1	0.19	<10	2.39	3366	<2	0.01	15	1371	27	0.96	<5	10	156	<5	0.10	<10	<10	168	<10	85	4
8V2690RA/RJ	HL08-16	84431	72.80	73.80	1.00	0.07	0.4	2.12	180	51	<0.5	<5	10.09	25	23	28	193	5.83	<1	0.19	<10	1.40	3042	<2	0.01	10	1004	100	2.01	<5	7	179	5	0.07	<10	<10	111	<10	2468	4
8V2690RA/RJ	HL08-16	84432	73.80	75.20	2.00	0.02	<0.1	2.91	97	63	0.8	<5	9.67	3	27	30	62	6.10	1	0.19	<10	2.17	3188	<2	0.01	14	1272	12	0.90	<5	11	172	<5	0.13	<10	<10	159	<10	183	5
8V2690RA/RJ	HL08-16	84433	75.80	77.00	1.20	0.01	0.2	2.67	83	61	0.8	<5	8.40	5	29	28	84	5.93	1	0.22	<10	2.03	2793	<2	0.01	13	1338	29	1.11	<5	10	144	5	0.13	<10	<10	149	<10	450	5
8V2690RA/RJ	HL08-16	84434	77.00	78.26	1.26	0.02	<0.1	2.70	70	56	0.7	<5	10.46	2	28	29	57	5.43	1	0.21	<10	2.14	3366	<2	0.01	13	1266	16	0.60	<5	10	182	<5	0.10	<10	<10	140	<10	72	4
8V2690RA/RJ	HL08-16	84435	78.26	79.58	1.32	0.02	<0.1	2.16	48	58	0.7	<5	11.25	1	24	31	13	4.47	1	0.39	<10	1.46	3027	<2	0.01	11	1025	5	0.67	<5	6	177	5	0.07	<10	<10	75	<10	38	4
8V2690RA/RJ	HL08-16	84436	79.58	81.30	1.72	0.01	<0.1	2.98	117	50	0.7	<5	10.20	2	28	38	58	6.00	1	0.22	<10	2.35	3170	<2	0.01	15	1289	13	0.57	<5	12	162	<5	0.09	<10	<10	164	<10	76	5
8V2690RA/RJ	HL08-16	84437	81.30	83.00	1.70	<0.01	<0.1	2.61	117	44	0.5	<5	10.03	3	27	35	64	5.73	1	0.18	<10	2.12	2867	<2	0.01	14	1208	14	0.97	5	11	149	<5	0.08	<10	<10	153	<10	159	4
8V2690RA/RJ	HL08-16	84438	83.00	84.80	1.80	<0.01	<0.1	2.60	80	49	0.5	<5	11.05	1	24	35	54	5.18	1	0.16	<10	2.11	3345	<2	0.01	13	1186	9	0.39	<5	12	157	<5	0.07	<10	<10	163	<10	50	4
8V2690RA/RJ	HL08-16	84439	84.80	85.40	0.60	0.18	4.8	1.57	2060	71	<0.5	<5	10.14	40	29	32	509	5.73	1	0.21	<10	1.85	3165	<2	0.01	13	1023	3240	1.39	16	11	395	<5	0.01	<10	<10	97	<10	4296	3
8V2690RA/RJ	HL08-16	84440	85.40	86.60	1.20	0.11	<0.1	2.90	843	56	0.6	<5	9.26	16	24	32	60	6.23	1	0.16	<10	2.24	3786	<2	0.01	16	1278	87	0.88	5	14	144	<5	0.09	<10	<10	190	<10	1688	4
8V2690RA/RJ	HL08-16	84441	86.60	87.83	1.23	0.87	3.3	2.37	2232	60	0.5	<5	5.18	23	29	40	187	6.63	1	0.17	<10	1.71	3071	<2	0.01	15	1267	707	2.35	15	10	77	<5	0.07	<10	<10	160	<10	2710	4
8V2690RA/RJ	HL08-16	84442	87.83	89.20	1.37	0.02	<0.1	2.62	116	51	0.7	<5	9.20	2	26	40	64	6.03	1	0.12	<10	2.10	3110	<2	0.01	14	1257	71	0.63	<5	16	102	<5	0.09	<10	<10	211	<10	160	5
8V2690RA/RJ	HL08-16	84443	89.20	90.60	1.40	0.02	1.2	2.97	84	48	0.8	<5	6.93	3	29	41	108	6.62	1	0.10	<10	2.47	2853	<2	0.01	15	1369	39	1.04	5	13	88	<5	0.10	<10	<10	220	<10	147	5
8V2690RA/RJ	HL08-16	84444	90.60	92.60	2.00	0.01	0.4	3.16	59	48	0.8	<5	8.84	3	30	44	75	7.03	1	0.07	<10	2.58	3148	<2	0.01	15	1421	34	1.70	<5	14	110	<5	0.11	<10	<10	243	<10	199	6
8V2690RA/RJ	HL08-16	84445	92.60	94.56	1.96	0.02	<0.1	2.45	62	73	0.7	<5	9.56	2	27	34	67	5.53	1	0.08	<10	1.95	2776	<2	0.01	13	1231	16	0.43	<5	14	123	<5	0.10	<10	<10	196	<10	66	6
8V2690RA/RJ	HL08-16	84446	94.56	96.60	2.04	0.03	1.0	2.62	73	69	0.7	<5	9.39	2	25	38	77	5.56	1	0.19	<10	2.01	2783	<2	0.01	12	1532	53	0.59	<5	12	166	<5	0.09	<10	<10	151	<10	236	4
8V2690RA/RJ	HL08-16	84447	96.60	98.60	2.00	0.02	1.4	1.52	164	76	<0.5	<5	11.63	5	22	32	40	5.26	<1	0.20	<10	1.54	3749	<2	0.01	46	1350	31	1.06	<5	8	262	<5	0.01	<10	<10	84	<10	338	2
8V2690RA/RJ	HL08-16	84448	98.60	100.60	2.00	0.04	0.6	2.60	133	53	0.5	<5	9.67	27	24	34	94	5.86	1	0.15	<10	2.06	3494	<2	0.01	13	1492	180	0.97	<5	9	195	<5	0.07	<10	<10	138	32	2609	3
8V2690RA/RJ	HL08-16	84449	100.60	101.90	1.30	0.02	0.5	2.31	185	57	0.7	<5	9.37	3	26	35	86	5.25	<1	0.19	<10	1.75	2988	<2	0.01	14	1606	25	0.97	<5	9	199	<5	0.11	<10	<10	140	<10	156	3
8V2690RA/RJ	HL08-16	84450	Blank	Blank		<0.01	<0.1	0.88	<5	246	0.7	<5	0.51	<1	8	93	1	2.13	<1	0.47	<10	0.60	597	<2	0.05	7	782	7	0.01	<5	2	38	<5	0.13	<10	<10	39	<10	72	2
8V2690RA/RJ	HL08-16	84451	101.90	103.15	1.25	0.11	1.3	2.84	2575	68	0.7	<5	5.22	47	29	33	116	7.00	<1	0.24	<10	2.09	2983	<2	0.01	22	1772	240	1.53	5	9	99	<5	0.12	<10	<10	157	13	965	3
8V2690RA/RJ	HL08-16	84452	103.15	105.1																																				

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																										
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
HL08-17 - Zone: Below Road, Pad 19: 434441E.6223925N, Elev: 945m, Az: 213, Dip: -52, EOH: 138.11m																																								
8V2596RA/RJ	HL08-17	84494	0.00	2.00	2.00	0.01	0.5	2.62	432	233	0.6	<5	7.01	7	29	47	80	5.60	1	0.18	<10	2.37	2538	<2	0.01	12	1815	49	1.48	<5	17	168	<5	0.08	<10	<10	221	<10	142	5
8V2596RA/RJ	HL08-17	84495	2.00	4.00	2.00	0.03	1.1	2.38	410	180	0.5	<5	9.09	6	28	42	93	5.64	1	0.17	<10	2.09	2642	<2	0.01	13	1787	66	1.91	<5	16	215	<5	0.06	<10	<10	215	<10	139	5
8V2596RA/RJ	HL08-17	84496	4.00	6.00	2.00	<0.01	0.9	2.51	134	271	0.5	<5	9.32	2	30	41	98	5.96	<1	0.11	<10	2.58	2925	<2	0.02	13	1772	51	1.56	<5	21	308	<5	0.06	<10	<10	218	<10	125	5
8V2596RA/RJ	HL08-17	84497	6.00	7.85	1.85	<0.01	0.5	3.13	53	103	0.7	<5	7.14	<1	32	51	95	6.47	<1	0.11	<10	3.03	2751	<2	0.02	14	1868	34	1.89	<5	23	178	<5	0.10	<10	<10	263	<10	80	6
8V2596RA/RJ	HL08-17	84498	7.85	8.78	0.93	0.06	21.3	2.14	2784	58	<0.5	>15.00	120	14	25	679	5.13	<1	0.11	<10	1.66	4223	<2	0.01	5	846	8088	1.78	46	9	1144	<5	<0.01	<10	<10	91	87	6270	3	
8V2596RA/RJ	HL08-17	84499	8.78	10.00	1.22	0.01	1.1	2.93	921	87	0.6	<5	8.14	17	25	46	85	5.72	<1	0.08	<10	2.75	3198	<2	0.01	12	1646	294	1.13	8	19	252	<5	0.08	<10	<10	249	<10	357	4
8V2596RA/RJ	HL08-17	84500	Blank	Blank	<0.01	<0.1	1.08	7	396	0.9	<5	0.76	<1	9	152	6	2.30	<1	0.51	<10	0.71	699	2	0.08	7	871	63	0.05	<5	3	53	<5	0.15	<10	<10	49	<10	113	2	
8V2596RA/RJ	HL08-17	84501	10.00	12.00	2.00	0.01	0.2	2.72	90	62	0.7	<5	9.58	2	31	47	114	5.97	1	0.05	<10	2.41	2693	<2	0.02	13	1773	92	1.53	<5	20	277	<5	0.11	<10	<10	278	<10	137	5
8V2596RA/RJ	HL08-17	84502	12.00	14.00	2.00	0.02	0.9	2.65	321	66	0.7	<5	8.82	5	28	53	97	5.50	1	0.11	<10	2.59	2669	<2	0.01	13	1816	79	1.72	5	16	222	<5	0.11	<10	<10	227	<10	143	5
8V2596RA/RJ	HL08-17	84503	14.00	16.00	2.00	0.03	1.0	2.57	345	52	0.6	<5	10.93	8	28	35	88	5.19	<1	0.13	<10	2.31	3058	<2	0.01	11	1577	121	1.22	<5	13	228	<5	0.09	<10	<10	181	<10	392	4
8V2596RA/RJ	HL08-17	84504	16.00	18.00	2.00	0.02	1.0	2.74	176	65	0.8	<5	9.60	4	28	42	81	5.56	<1	0.21	<10	2.23	2929	<2	0.01	13	1767	80	1.03	<5	13	206	<5	0.11	<10	<10	183	<10	212	4
8V2596RA/RJ	HL08-17	84505	18.00	20.00	2.00	0.05	1.4	2.68	104	57	0.6	<5	8.73	15	29	40	193	5.40	<1	0.20	<10	2.13	2917	<2	0.01	12	1717	108	0.81	<5	11	165	<5	0.09	<10	<10	167	19	1260	3
8V2596RA/RJ	HL08-17	84506	20.00	22.00	2.00	0.05	3.3	2.73	162	61	0.5	<5	6.90	24	24	39	139	5.96	<1	0.20	<10	2.04	2794	<2	0.01	11	1561	1167	1.59	<5	11	126	<5	0.08	<10	<10	165	28	2059	4
8V2596RA/RJ	HL08-17	84507	22.00	24.00	2.00	0.05	1.1	2.92	147	59	0.6	<5	6.28	6	31	44	104	6.52	<1	0.24	<10	2.36	2513	<2	0.01	14	1798	70	2.20	<5	11	113	<5	0.08	<10	<10	174	<10	547	4
8V2596RA/RJ	HL08-17	84508	24.00	26.00	2.00	0.05	0.6	2.82	367	46	0.6	<5	10.84	6	23	39	71	5.59	<1	0.17	<10	2.40	2697	<2	0.01	12	1594	32	0.84	<5	15	184	<5	0.08	<10	<10	201	<10	175	4
8V2596RA/RJ	HL08-17	84509	26.00	28.00	2.00	0.05	0.3	2.28	62	41	0.7	<5	11.77	1	23	42	46	5.09	1	0.12	<10	1.81	2705	<2	0.01	13	1558	17	0.53	<5	18	218	<5	0.07	<10	<10	209	<10	120	4
8V2596RA/RJ	HL08-17	84510	28.00	29.00	1.00	0.03	0.6	2.70	79	42	0.7	<5	10.91	5	27	41	80	5.44	<1	0.12	<10	2.34	2767	<2	0.01	13	1592	17	0.48	<5	18	187	<5	0.08	<10	<10	220	<10	447	4
8V2596RA/RJ	HL08-17	84511	29.00	31.00	2.00	0.05	1.2	2.44	119	46	0.7	<5	10.60	5	30	37	102	5.12	<1	0.15	<10	2.02	2586	<2	0.01	12	1644	151	0.94	<5	16	185	<5	0.09	<10	<10	198	<10	352	4
8V2596RA/RJ	HL08-17	84512	31.00	33.00	2.00	0.02	1.0	2.50	217	70	0.6	<5	6.81	8	27	44	101	5.67	<1	0.17	<10	1.97	2298	<2	0.01	14	1753	398	1.64	<5	13	106	<5	0.08	<10	<10	202	<10	512	4
8V2596RA/RJ	HL08-17	84513	33.00	33.95	0.95	0.01	<0.1	2.65	62	48	0.8	<5	8.46	1	30	47	80	6.06	<1	0.09	<10	2.23	2366	<2	0.02	14	1861	20	1.37	<5	22	146	<5	0.12	<10	<10	279	<10	129	5
8V2596RA/RJ	HL08-17	84514	33.95	34.70	0.75	0.01	0.1	2.55	44	36	1.0	<5	11.09	8	22	47	16	4.97	<1	0.08	<10	2.28	2143	<2	0.01	13	1547	438	0.20	<5	20	198	<5	0.15	<10	<10	220	11	722	7
8V2596RA/RJ	HL08-17	84515	34.70	36.00	1.30	0.02	0.2	2.57	1818	59	0.8	<5	8.25	30	31	40	74	5.47	<1	0.07	<10	2.46	2652	<2	0.02	13	1809	67	1.13	21	10	172	<5	0.10	<10	<10	207	<10	192	6
8V2596RA/RJ	HL08-17	84516	36.00	38.00	2.00	0.02	<0.1	2.66	64	52	0.6	<5	5.33	3	28	59	58	5.86	<1	0.06	<10	2.29	2648	<2	0.01	14	1291	61	1.00	<5	15	96	<5	0.12	<10	<10	225	<10	336	6
8V2596RA/RJ	HL08-17	84517	38.00	40.00	2.00	<0.01	0.4	2.87	94	50	0.6	<5	5.89	11	30	54	87	6.47	<1	0.04	<10	2.59	2731	<2	0.02	14	1286	666	1.58	<5	19	109	<5	0.09	<10	<10	263	<10	1112	5
8V2596RA/RJ	HL08-17	84518	40.00	41.39	1.39	0.01	<0.1	3.11	496	55	<0.5	<5	4.57	7	29	49	90	7.01	<1	0.04	<10	2.86	2835	<2	0.01	14	1356	209	1.72	<5	21	88	<5	0.04	<10	<10	275	<10	773	4
8V2596RA/RJ	HL08-17	84519	41.39	42.03	0.64	0.02	1.7	1.98	1326	121	<0.5	<5	10.46	56	25	37	561	6.03	<1	0.16	<10	1.85	3713	<2	0.01	14	1014	1382	1.39	18	16	293	<5	0.01	<10	<10	141	<10	5842	3
8V2596RA/RJ	HL08-17	84520	42.03	44.00	1.97	0.01	<0.1	2.51	114	83	0.6	<5	7.06	7	28	49	99	6.25	1	0.07	<10	2.16	2903	<2	0.01	13	1311	179	1.68	<5	20	137	<5	0.08	<10	<10	246	<10	771	6
8V2596RA/RJ	HL08-17	84521	44.00	46.00	2.00	0.01	<0.1	2.76	181	54	0.5	<5	6.66	10	28	58	91	6.56	1	0.05	<10	2.41	2714	<2	0.01	14	1299	216	1.58	<5	20	123	<5	0.08	<10	<10	255	<10	1083	5
8V2596RA/RJ	HL08-17	84522	46.00	47.00	1.00	0.01	<0.1	2.95	68	51	0.6	<5	5.19	5	34	56	96	7.01	<1	0.03	<10	2.69	2569	<2	0.02	16	1352	71	1.96	<5	21	91	<5	0.13	<10	<10	291	<10	635	6
8V2596RA/RJ	HL08-17	84523	47.00	48.61	1.61	0.01	<0.1	2.75	46	50	0.7	<5	6.28	3	30	51	87	6.74	<1	0.04	<10	2.46	2577	<																

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	Zn ppm	Zr ppm	
8V2690RA/RJ	HL08-17	84565	110.00	111.00	1.00	0.01	<0.1	2.39	101	59	0.8	<5	11.77	1	28	32	40	5.59	<1	0.21	<10	1.82	3865	<2	0.01	12	1236	16	1.24	<5	10	286	<5	0.13	<10	<10	126	<10	55	5
8V2690RA/RJ	HL08-17	84566	111.00	112.00	1.00	0.01	<0.1	2.31	224	53	0.8	<5	10.97	2	25	35	14	4.53	<1	0.20	<10	1.86	3559	<2	0.01	12	1161	63	0.46	<5	10	201	<5	0.11	<10	<10	120	<10	141	4
8V2690RA/RJ	HL08-17	84567	112.00	113.00	1.00	0.02	0.7	2.15	128	54	0.6	<5	9.82	8	24	43	109	5.26	<1	0.21	<10	1.67	3338	<2	0.01	14	1097	301	1.72	<5	8	183	<5	0.08	<10	<10	93	<10	764	4
8V2690RA/RJ	HL08-17	84568	113.00	114.00	1.00	0.04	0.5	2.26	153	63	0.5	<5	10.79	6	27	32	65	6.23	<1	0.27	<10	1.59	3975	<2	0.01	13	1052	321	2.74	6	7	227	<5	0.10	<10	<10	99	<10	512	4
8V2690RA/RJ	HL08-17	84569	114.00	115.00	1.00	0.01	0.3	3.13	99	130	0.7	<5	6.22	5	32	37	65	7.26	<1	0.32	<10	2.31	3334	<2	0.01	15	1450	241	2.22	<5	10	134	<5	0.13	<10	<10	155	<10	353	5
8V2690RA/RJ	HL08-17	84570	115.00	116.13	1.13	0.03	0.7	2.65	104	110	0.5	<5	7.48	6	28	33	102	6.30	<1	0.24	<10	2.03	3179	<2	0.01	14	1338	234	1.98	6	8	155	<5	0.09	<10	<10	135	<10	561	4
8V2690RA/RJ	HL08-17	84571	116.13	117.50	1.37	0.01	<0.1	2.19	217	60	0.5	<5	9.58	2	28	31	60	5.08	<1	0.24	<10	1.71	2173	<2	0.01	12	1311	21	1.48	5	9	181	<5	0.08	<10	<10	117	<10	111	3
8V2690RA/RJ	HL08-17	84572	117.50	118.50	1.00	0.01	<0.1	2.31	117	58	<0.5	<5	8.16	4	25	31	78	5.36	<1	0.23	<10	1.83	2551	<2	0.01	12	1213	15	1.54	6	9	167	<5	0.06	<10	<10	124	<10	283	3
8V2690RA/RJ	HL08-17	84573	118.50	119.50	1.00	0.02	0.2	2.56	98	81	0.6	<5	7.72	3	29	40	80	5.74	<1	0.19	<10	2.23	2690	<2	0.01	16	1291	12	1.68	6	9	174	<5	0.09	<10	<10	130	<10	170	4
8V2690RA/RJ	HL08-17	84574	119.50	120.50	1.00	<0.01	<0.1	3.13	76	120	0.6	<5	7.39	4	28	55	81	6.29	<1	0.23	<10	2.74	2962	<2	0.01	17	1339	6	1.27	<5	10	167	<5	0.08	<10	<10	151	<10	322	4
8V2690RA/RJ	HL08-17	84575	120.50	121.50	1.00	0.03	<0.1	2.07	321	57	<0.5	<5	10.62	1	25	35	56	4.69	<1	0.20	<10	1.70	3423	<2	0.01	13	1141	8	1.31	6	8	239	<5	0.05	<10	<10	125	<10	59	3
8V2690RA/RJ	HL08-17	84575A	Blank	Blank		<0.01	<0.1	1.11	<5	240	0.7	<5	0.72	<1	8	90	<1	2.14	<1	0.54	<10	0.67	630	<2	0.08	6	705	3	0.02	<5	3	66	6	0.13	<10	<10	45	<10	50	3
8V2690RA/RJ	HL08-17	84576	121.50	122.50	1.00	0.05	0.8	1.46	177	59	<0.5	<5	6.90	7	29	25	98	6.11	<1	0.23	<10	1.19	2908	<2	0.01	15	1285	32	4.06	8	6	177	<5	0.06	<10	<10	102	<10	598	4
8V2690RA/RJ	HL08-17	84577	122.50	123.50	1.00	0.04	0.7	1.40	125	72	<0.5	<5	6.83	6	29	30	89	6.06	<1	0.28	<10	1.11	2953	<2	0.01	15	1354	40	4.68	8	6	175	<5	0.07	<10	<10	91	<10	547	4
8V2690RA/RJ	HL08-17	84578	123.50	124.00	0.50	0.05	1.3	1.44	151	71	0.5	<5	6.20	9	36	29	123	6.95	<1	0.25	<10	1.20	3174	<2	0.01	16	1338	36	>5.00	6	6	153	<5	0.12	<10	<10	111	<10	788	4
8V2690RA/RJ	HL08-17	84579	124.00	124.50	0.50	0.06	0.9	1.51	173	83	0.5	<5	8.24	13	30	35	74	6.79	<1	0.29	<10	1.26	3809	<2	0.01	16	1379	42	>5.00	9	7	199	<5	0.10	<10	<10	114	<10	1401	5
8V2690RA/RJ	HL08-17	84580	124.50	125.00	0.50	0.07	3.3	0.90	146	86	0.5	<5	8.67	8	31	27	60	6.28	<1	0.32	<10	0.64	2908	<2	0.01	16	1358	604	>5.00	14	6	180	<5	0.09	<10	<10	76	<10	782	4
8V2690RA/RJ	HL08-17	84581	125.00	125.50	0.50	0.07	0.5	0.43	104	73	0.5	<5	9.55	1	25	21	68	3.63	<1	0.33	<10	0.17	2507	<2	0.01	12	1123	47	3.24	14	5	212	<5	0.06	<10	<10	25	<10	52	2
8V2690RA/RJ	HL08-17	84582	125.50	126.00	0.50	0.10	1.6	0.96	234	59	0.5	<5	5.23	2	24	27	65	5.47	<1	0.27	<10	0.82	2349	<2	0.01	13	1038	62	4.47	15	5	134	<5	0.08	<10	<10	43	<10	71	3
8V2690RA/RJ	HL08-17	84583	126.00	126.50	0.50	0.12	35.1	1.97	402	33	<0.5	<5	10.78	46	18	39	417	6.73	<1	0.12	<10	2.29	5243	<2	0.01	10	706	2859	4.83	39	7	295	<5	0.06	<10	<10	80	<10	4366	4
8V2690RA/RJ	HL08-17	84584	126.50	127.00	0.50	0.16	4.5	1.47	320	54	0.5	<5	5.19	4	27	28	82	7.96	<1	0.29	<10	1.50	2645	<2	0.01	13	1184	313	>5.00	21	5	151	<5	0.10	<10	<10	59	<10	265	5
8V2690RA/RJ	HL08-17	84585	127.00	127.50	0.50	0.08	1.4	0.99	170	69	0.5	<5	7.59	2	27	30	73	5.98	<1	0.30	<10	0.85	2761	<2	0.01	14	1182	96	>5.00	12	5	184	<5	0.09	<10	<10	46	<10	93	4
8V2690RA/RJ	HL08-17	84586	127.50	128.00	0.50	0.06	1.4	2.18	151	60	<0.5	<5	8.90	4	25	38	59	6.23	<1	0.26	<10	2.36	3703	<2	0.01	12	1146	157	4.62	7	6	240	<5	0.06	<10	<10	95	<10	310	4
8V2690RA/RJ	HL08-17	84587	128.00	128.50	0.50	0.03	1.2	1.53	124	74	0.5	<5	5.90	2	31	43	74	5.97	<1	0.36	<10	1.42	2519	<2	0.01	16	1390	93	4.97	10	6	165	<5	0.10	<10	<10	73	<10	131	4
8V2690RA/RJ	HL08-17	84588	128.50	129.00	0.50	0.07	1.9	1.54	104	59	0.5	<5	5.00	4	28	32	93	6.75	<1	0.31	<10	1.47	2462	<2	0.01	14	1196	201	>5.00	15	5	148	<5	0.10	<10	<10	85	<10	290	4
8V2690RA/RJ	HL08-17	84589	129.00	129.50	0.50	0.11	2.7	1.25	189	64	<0.5	<5	5.67	8	24	40	81	6.01	<1	0.28	<10	1.17	2638	<2	0.01	12	1123	406	4.67	13	5	142	<5	0.08	<10	<10	61	<10	901	4
8V2690RA/RJ	HL08-17	84590	129.50	130.00	0.50	0.08	2.1	1.28	182	59	<0.5	<5	4.86	4	27	24	73	6.62	<1	0.33	<10	1.12	2304	<2	0.01	13	1319	230	>5.00	13	4	121	<5	0.07	<10	<10	54	<10	281	4
8V2690RA/RJ	HL08-17	84591	130.00	130.50	0.50	0.11	2.1	1.48	493	65	0.5	<5	6.28	6	29	35	79	7.02	<1	0.31	<10	1.38	2984	<2	0.01	14	1273	215	>5.00	12	5	154	<5	0.09	<10	<10	71	<10	542	4
8V2690RA/RJ	HL08-17	84592	130.50	131.00	0.50	0.05	1.5	1.96	129	89	<0.5	<5	9.02	2	22	53	59	5.67	<1	0.27	<10	2.08	4428	<2	0.01	11	1036	87	3.92	11	6	236	<5	0.06	<10	<10	73	<10	144	4
8V2690RA/RJ	HL08-17	84593	131.00	131.50	0.50	0.09	1.0	1.34	204	76	<0.5	<5	10.64	2	23	50	68	5.82	<1	0.28	<10	1.28	3678	<2	0.01	12	1010	57	4.66	15	6	203	<5	0.07	<10	<10	55	<1		

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																												
					Au g/t	Ag g/t	Al %	As ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm			
8V2690RA/RJ	HL08-18	84635	48.69	49.40	0.71	0.01	0.4	2.79	63	64	1.0	<5	8.32	2	27	52	61	5.43	<1	0.06	<10	2.59	2950	<2	0.01	12	1590	104	1.43	<5	19	243	<5	0.17	<10	<10	228	<10	245	8	
8V2690RA/RJ	HL08-18	84636	49.40	50.58	1.18	0.05	7.0	3.26	1752	83	<0.5	<5	6.68	66	25	39	140	6.43	<1	0.15	<10	2.85	2851	<2	0.01	10	1657	2006	1.36	8	16	42	<5	0.01	<10	<10	208	39	3584	4	
8V2690RA/RJ	HL08-18	84637	50.58	52.00	1.42	0.01	0.4	2.72	101	68	0.8	<5	7.23	2	21	45	57	4.80	<1	0.14	<10	2.28	2762	<2	0.01	12	1552	59	0.55	<5	16	209	<5	0.11	<10	<10	198	<10	168	4	
8V2690RA/RJ	HL08-18	84638	52.00	53.52	1.52	0.03	1.3	2.33	141	68	0.7	<5	6.60	4	29	43	140	6.41	<1	0.10	<10	2.74	2668	<2	0.01	12	1595	587	1.44	<5	18	140	<5	0.11	<10	<10	234	<10	323	5	
8V2690RA/RJ	HL08-18	84639	53.52	54.43	0.91	0.01	<0.1	2.38	38	85	0.9	<5	9.22	<1	22	43	38	5.00	<1	0.11	<10	2.00	2045	<2	0.01	10	1454	19	0.29	<5	18	159	<5	0.13	<10	<10	207	<10	85	6	
8V2690RA/RJ	HL08-18	84640	54.43	56.36	1.93	0.01	1.2	2.69	107	68	0.8	<5	7.00	15	25	37	118	5.52	<1	0.21	<10	1.88	2663	<2	0.01	11	1588	393	1.31	<5	14	114	<5	0.11	<10	<10	181	16	1318	4	
8V2690RA/RJ	HL08-18	84641	56.36	58.00	1.64	0.01	0.8	2.03	51	53	0.9	<5	9.24	<1	19	37	93	4.49	<1	0.12	<10	1.46	2370	<2	0.01	9	1461	12	0.56	<5	14	160	<5	0.13	<10	<10	188	<10	84	5	
8V2690RA/RJ	HL08-18	84642	58.00	60.00	2.00	<0.01	0.7	2.37	71	48	0.8	<5	9.69	<1	28	43	74	4.92	<1	0.07	<10	1.80	2124	<2	0.01	10	1489	17	0.70	<5	12	177	<5	0.12	<10	<10	197	<10	70	6	
8V2690RA/RJ	HL08-18	84643	60.00	62.00	2.00	0.01	2.2	2.34	81	51	0.9	<5	8.88	2	27	45	313	4.59	<1	0.08	<10	1.81	2272	<2	0.01	11	1559	46	0.95	<5	10	235	<5	0.13	<10	<10	166	<10	270	6	
8V2690RA/RJ	HL08-18	84644	62.00	64.00	2.00	0.01	0.8	2.68	117	74	0.9	<5	8.87	3	28	39	67	4.90	<1	0.07	<10	2.43	2732	<2	0.01	11	1526	69	0.56	<5	11	225	<5	0.14	<10	<10	195	<10	272	6	
8V2690RA/RJ	HL08-18	84645	64.00	66.00	2.00	<0.01	0.6	2.64	41	162	0.8	<5	5.46	1	27	50	88	5.71	<1	0.05	<10	2.45	2323	<2	0.03	12	1709	86	1.81	<5	11	118	<5	0.14	<10	<10	224	<10	214	7	
8V2690RA/RJ	HL08-18	84646	66.00	66.49	0.49	0.01	<0.1	2.97	30	78	0.7	<5	6.18	<1	19	39	64	5.26	<1	0.05	<10	3.04	2114	<2	0.02	11	1694	22	0.73	<5	15	146	<5	0.10	<10	<10	230	<10	71	6	
8V2690RA/RJ	HL08-18	84647	66.49	68.49	2.00	0.01	0.2	2.73	68	62	<0.5	<5	7.60	<1	26	43	58	5.12	<1	0.09	<10	2.47	2337	<2	0.02	11	1524	28	0.93	<5	15	220	<5	0.02	<10	<10	209	<10	91	3	
8V2690RA/RJ	HL08-18	84648	68.49	70.49	2.00	0.01	0.5	3.53	96	65	<0.5	<5	4.89	3	27	42	93	6.18	<1	0.09	<10	3.20	2409	<2	0.02	11	1661	43	0.88	<5	16	86	<5	0.04	<10	<10	244	<10	310	4	
8V2690RA/RJ	HL08-18	84649	70.49	72.49	2.00	0.15	1.9	2.90	70	258	<0.5	<5	5.03	5	24	53	109	5.79	<1	0.18	<10	2.50	2118	<2	0.03	15	1606	162	1.57	<5	15	105	<5	0.03	<10	<10	219	<10	532	4	
8V2690RA/RJ	HL08-18	84650	Std	PM1110			1.68	174.0	0.98	224	229	0.6	79	5.42	5	17	23	3589	3.57	4	0.18	<10	0.20	711	77	0.03	33	744	228	1.40	236	2	200	<5	0.09	<10	<10	25	18	242	12
8V2690RA/RJ	HL08-18	84651	72.49	74.21	1.72	0.01	0.9	3.01	114	64	<0.5	<5	5.52	8	26	39	92	5.98	<1	0.16	<10	2.61	2438	<2	0.01	12	1630	86	1.73	<5	13	118	<5	0.01	<10	<10	205	11	849	3	
8V2690RA/RJ	HL08-18	84652	74.21	76.00	1.79	0.11	3.6	1.84	1434	118	<0.5	<5	7.98	47	21	28	111	5.24	<1	0.25	<10	1.75	3632	<2	0.01	9	1430	1019	1.99	5	10	280	<5	<0.01	<10	<10	103	27	2421	3	
8V2690RA/RJ	HL08-18	84653	76.00	77.33	1.33	0.06	4.0	2.19	1866	119	<0.5	<5	9.24	14	26	45	201	5.78	<1	0.19	<10	1.79	3399	<2	0.01	14	1208	712	1.40	19	13	214	<5	<0.01	<10	<10	165	<10	1411	3	
8V2690RA/RJ	HL08-18	84654	77.33	79.33	2.00	0.14	1.7	2.29	210	141	<0.5	<5	6.84	3	28	71	94	6.58	<1	0.19	<10	1.89	2466	<2	0.02	15	1326	93	2.84	8	14	120	<5	0.02	<10	<10	201	<10	120	4	
8V2690RA/RJ	HL08-18	84655	79.33	81.33	2.00	0.04	0.4	2.29	194	71	0.6	<5	6.12	2	30	59	100	6.07	<1	0.19	<10	1.89	1765	<2	0.02	16	1423	33	2.27	9	17	105	<5	0.07	<10	<10	231	<10	63	5	
8V2690RA/RJ	HL08-18	84655A	81.33	83.33	2.00	0.02	<0.1	2.32	214	51	0.6	<5	7.21	2	28	68	83	6.30	<1	0.09	<10	2.11	1924	<2	0.01	15	1219	22	2.47	9	18	104	<5	0.07	<10	<10	228	<10	54	5	
8V2690RA/RJ	HL08-18	84656	83.33	85.33	2.00	0.02	<0.1	2.53	43	52	0.6	<5	7.59	2	30	52	61	5.95	<1	0.09	<10	2.38	1993	<2	0.02	15	1250	12	1.85	<5	18	123	<5	0.09	<10	<10	237	<10	57	6	
8V2690RA/RJ	HL08-18	84657	85.33	87.33	2.00	0.01	<0.1	2.66	63	46	0.7	<5	7.80	2	30	52	70	6.16	<1	0.09	<10	2.52	2042	<2	0.02	15	1259	33	2.00	<5	18	118	<5	0.11	<10	<10	237	<10	71	6	
8V2690RA/RJ	HL08-18	84658	87.33	89.33	2.00	0.02	0.2	2.70	37	43	0.7	<5	4.88	2	36	54	118	6.98	<1	0.05	<10	2.79	1762	<2	0.03	17	1421	29	2.62	5	16	97	<5	0.12	<10	<10	270	<10	71	8	
8V2690RA/RJ	HL08-18	84659	89.33	91.33	2.00	0.02	<0.1	2.52	48	65	0.7	<5	5.77	2	32	58	93	6.60	<1	0.06	<10	2.70	1703	<2	0.02	15	1298	15	2.64	5	14	113	<5	0.12	<10	<10	244	<10	47	8	
8V2690RA/RJ	HL08-18	84660	91.33	93.33	2.00	0.01	<0.1	2.85	652	52	0.6	<5	8.00	2	31	56	78	6.78	<1	0.05	<10	2.86	2208	<2	0.02	15	1363	16	2.24	12	21	131	<5	0.10	<10	<10	277	<10	57	7	
8V2690RA/RJ	HL08-18	84661	93.33	95.33	2.00	0.01	<0.1	2.89	52	50	0.7	<5	4.72	2	31	56	90	6.97	<1	0.05	<10	3.05	1960	<2	0.02	15	1324	22	2.46	6	24	96	<5	0.10	<10	<10	282	<10	103	7	
8V2690RA/RJ	HL08-18	84662	95.33	97.33	2.00	0.01	0.2	2.11	31	50	0.5	<5	4.12	2	36	39	82	5.71	<1	0.07	<10	2.10	1480	<2	0.02	13	1116	25	2.46	5	19	85	<5	0.08	<10	<10	217	<10	74	6	
8V2690RA/RJ	HL08-18	84663	97.33	99.33	2.00	0.03	3.1	1.30	456	130	<0.5	<5	5.99	2	33	67	213	6.32	<1	0.33	<10	1.53	1822	<2	0.02	17	1335	38	3.08	22	13	319	<5	0.01	<10	<10	99	<10	83	4	

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																										
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V2698RA/RJ	HL08-18	84706	163.62	165.62	2.00	<0.01	0.9	2.37	42	95	<0.5	<5	9.16	1	25	29	78	5.56	<1	0.28	<10	1.92	1923	<2	0.01	13	1379	4	1.60	5	6	171	8	0.01	<10	<10	109	<10	53	4
8V2698RA/RJ	HL08-18	84707	163.62	167.62	2.00	<0.01	1.0	2.21	68	122	<0.5	<5	5.58	1	27	24	88	6.42	<1	0.34	<10	1.84	1636	<2	0.01	12	1568	5	3.32	<5	6	124	7	0.01	<10	<10	103	<10	54	5
8V2698RA/RJ	HL08-18	84708	167.62	169.62	2.00	0.01	0.7	2.51	43	100	<0.5	<5	6.81	1	27	30	79	6.53	<1	0.23	<10	2.50	1878	<2	0.02	13	1478	<2	1.91	7	9	185	8	0.01	<10	<10	137	<10	70	4
8V2698RA/RJ	HL08-18	84709	169.62	171.38	1.76	0.02	0.4	1.67	58	79	<0.5	<5	13.94	1	21	24	60	4.69	<1	0.20	10	1.47	2744	<2	0.02	9	1182	5	1.34	<5	7	287	11	0.01	<10	<10	93	<10	62	3
8V2698RA/RJ	HL08-18	84710	171.38	173.28	1.90	0.01	1.1	1.91	69	90	<0.5	<5	12.65	1	25	23	69	5.26	<1	0.23	11	1.56	2701	<2	0.01	10	1242	7	2.33	<5	7	253	15	0.01	<10	<10	94	<10	69	4
8V2698RA/RJ	HL08-18	84711	173.28	175.29	2.01	0.01	0.7	2.47	111	117	<0.5	<5	11.20	1	24	30	74	5.55	<1	0.28	11	2.01	2588	<2	0.02	11	1456	4	1.61	<5	8	209	12	0.02	<10	<10	118	<10	81	4
8V2698RA/RJ	HL08-18	84712	175.29	177.39	2.10	0.02	0.7	2.66	75	97	<0.5	<5	10.61	2	26	35	78	5.92	<1	0.20	10	2.18	2335	<2	0.02	13	1454	2	1.26	5	10	195	10	0.02	<10	<10	159	<10	136	4
8V2698RA/RJ	HL08-18	84713	177.39	178.15	0.76	<0.01	0.6	1.59	59	267	<0.5	<5	8.84	3	22	29	70	4.91	1	0.26	<10	1.54	1846	<2	0.02	11	1306	9	1.30	<5	7	188	5	<0.01	<10	<10	91	<10	114	4
8V2698RA/RJ	HL08-18	84714	178.15	180.15	2.00	0.01	1.2	2.08	88	193	<0.5	<5	7.22	2	25	30	91	5.61	1	0.26	<10	1.64	1845	<2	0.02	11	1416	9	1.84	<5	10	161	8	0.01	<10	<10	128	<10	138	4
8V2698RA/RJ	HL08-18	84715	180.15	182.15	2.00	0.02	0.8	1.68	43	247	<0.5	<5	9.75	2	22	31	85	4.86	1	0.25	10	1.55	2307	<2	0.02	10	1224	12	1.39	<5	9	206	10	0.01	<10	<10	103	<10	112	4
8V2698RA/RJ	HL08-18	84716	182.15	184.49	2.34	0.03	1.0	1.42	250	175	<0.5	<5	8.33	6	22	24	66	4.75	1	0.36	<10	1.20	2130	<2	0.01	9	1245	254	1.90	9	7	179	7	0.01	<10	<10	74	<10	558	3
8V2698RA/RJ	HL08-18	84717	184.49	186.50	2.01	0.02	0.8	1.76	52	194	<0.5	<5	10.10	2	21	25	67	4.65	2	0.30	<10	1.29	2111	<2	0.01	10	1252	65	1.55	<5	6	177	10	0.01	<10	<10	72	<10	90	3
8V2698RA/RJ	HL08-18	84718	186.50	188.50	2.00	0.04	2.7	1.71	154	82	<0.5	<5	7.45	3	24	23	71	5.31	1	0.50	<10	1.03	1905	<2	0.01	11	1356	159	3.56	9	6	148	8	0.02	<10	<10	77	<10	174	4
8V2698RA/RJ	HL08-18	84719	188.50	190.50	2.00	0.03	1.4	2.18	61	126	<0.5	<5	7.29	2	24	32	76	5.56	1	0.33	<10	1.66	1798	<2	0.02	10	1353	124	2.43	<5	8	150	10	0.05	<10	<10	110	<10	130	5
8V2698RA/RJ	HL08-18	84720	190.50	192.50	2.00	0.02	1.0	2.19	32	168	<0.5	<5	9.15	2	24	27	75	5.30	<1	0.20	<10	1.66	1777	<2	0.02	10	1317	65	1.63	<5	9	172	9	0.07	<10	<10	123	<10	89	4
8V2698RA/RJ	HL08-18	84721	192.50	194.50	2.00	0.02	0.9	2.02	35	275	<0.5	<5	11.38	3	21	37	67	4.80	2	0.18	10	1.48	2258	<2	0.02	9	1211	120	1.12	<5	10	204	11	0.03	<10	<10	134	<10	143	4
8V2698RA/RJ	HL08-18	84722	194.50	196.50	2.00	0.03	0.5	2.31	76	153	<0.5	<5	10.63	2	22	34	69	5.33	1	0.21	<10	1.60	2774	<2	0.01	10	1303	68	1.01	<5	9	189	8	0.01	<10	<10	126	<10	130	4
8V2698RA/RJ	HL08-18	84723	196.50	197.73	1.23	0.01	0.4	2.39	274	225	<0.5	<5	8.94	2	22	34	59	4.91	1	0.22	<10	1.84	2233	<2	0.01	9	1326	107	0.69	<5	9	172	10	0.03	<10	<10	129	<10	97	4
8V2698RA/RJ	HL08-18	84724	197.73	198.73	1.00	0.02	0.9	2.11	1064	171	<0.5	<5	6.65	2	22	33	80	5.06	<1	0.21	<10	1.74	1664	<2	0.01	9	1336	86	1.60	<5	8	130	6	0.03	<10	<10	125	<10	73	4
8V2698RA/RJ	HL08-18	84725	Blank	Blank	Blank	0.01	1.6	1.16	<5	567	0.6	<5	0.60	3	8	191	4	2.12	1	0.50	11	0.62	583	2	0.10	7	747	279	0.03	<5	3	80	<5	0.15	<10	<10	43	<10	210	4
8V2698RA/RJ	HL08-18	84726	198.73	200.24	1.51	0.03	0.7	2.11	4677	165	<0.5	<5	8.03	1	23	29	70	5.23	<1	0.22	<10	1.72	1810	<2	0.01	10	1293	81	1.66	5	8	150	11	0.03	<10	<10	116	<10	67	4
8V2698RA/RJ	HL08-18	84727	200.24	201.46	1.22	0.03	0.6	2.51	1059	104	<0.5	<5	10.25	3	20	36	63	5.20	1	0.28	<10	1.83	2280	<2	0.01	9	1305	7	0.75	6	10	176	13	0.01	<10	<10	112	<10	268	4
8V2698RA/RJ	HL08-18	84728	201.46	203.46	2.00	0.01	1.1	2.36	435	135	<0.5	<5	9.86	1	22	27	85	4.76	<1	0.34	<10	1.66	2351	<2	0.01	10	1272	11	0.91	5	9	179	14	0.04	<10	<10	109	<10	37	4
8V2698RA/RJ	HL08-18	84729	203.46	205.50	2.04	<0.01	0.2	2.58	162	102	<0.5	<5	9.53	1	25	36	60	5.19	<1	0.24	<10	2.20	2227	<2	0.01	11	1250	7	1.13	<5	11	192	10	0.06	<10	<10	144	<10	50	5
8V2698RA/RJ	HL08-18	84730	205.50	207.50	2.00	0.03	0.8	2.66	177	101	0.5	<5	9.53	1	27	36	91	5.68	1	0.25	<10	2.21	2538	<2	0.01	9	1474	12	1.20	<5	11	174	11	0.09	<10	<10	160	<10	59	5
8V2698RA/RJ	HL08-18	84731	207.50	209.50	2.00	0.02	1.3	2.79	63	115	<0.5	<5	5.78	3	25	34	82	6.08	1	0.23	<10	2.33	2181	<2	0.02	12	1518	64	1.47	8	10	125	8	0.03	<10	<10	171	<10	238	5
8V2698RA/RJ	HL08-18	84732	209.50	211.50	2.00	0.01	1.1	2.58	83	117	<0.5	<5	6.50	4	24	29	79	5.74	1	0.17	<10	2.27	2458	<2	0.02	10	1409	126	1.49	<5	10	147	8	0.03	<10	<10	155	<10	356	5
8V2698RA/RJ	HL08-18	84733	211.50	213.50	2.00	0.01	1.0	3.00	47	231	<0.5	<5	6.33	3	25	42	75	5.97	1	0.09	<10	2.94	2019	<2	0.02	11	1381	103	1.10	<5	14	131	10	0.02	<10	<10	206	<10	242	5
8V2698RA/RJ	HL08-18	84734	213.50	215.50	2.00	<0.01	0.5	2.76	41	252	<0.5	<5	7.70	1	24	33	74	5.51	1	0.23	<10	2.50	1883	<2	0.02	10	1364	35	1.33	5	11	171	9	0.01	<10	<10	153	<10	118	4
8V2698RA/RJ	HL08-18	84735	215.50	217.00	1.50	0.01	1.3	3.27	132	149	<0.5	<5	5.87	4	23	29	81	5.28	<1	0.30	<10	2.08	2320	<2	0.01	10	1277	165	1.63	6	8	124	9	0.01	<10	<10	1			

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																										
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V2690RA/RJ	HL08-19	84777	24.77	26.77	2.00	0.09	0.5	1.21	45	71	<0.5	<5	2.64	1	10	76	67	3.79	<1	0.21	<10	0.74	11340	16	0.02	2	927	8	0.65	<5	4	108	<5	0.01	<10	<10	47	<10	59	2
8V2690RA/RJ	HL08-19	84778	26.77	28.77	2.00	0.11	0.3	0.77	29	77	<0.5	<5	2.38	1	8	133	26	3.09	<1	0.24	<10	0.59	1170	8	0.02	4	737	18	0.58	<5	4	107	<5	0.01	<10	<10	26	<10	68	2
8V2690RA/RJ	HL08-19	84779	28.77	30.77	2.00	0.08	0.3	0.75	78	60	<0.5	<5	1.81	1	8	122	15	2.92	<1	0.20	<10	0.47	968	13	0.02	3	669	11	0.74	<5	3	60	<5	0.01	<10	<10	26	<10	36	2
8V2690RA/RJ	HL08-19	84780	30.77	32.77	2.00	0.04	0.2	1.16	42	99	<0.5	<5	3.37	1	9	135	20	3.60	<1	0.24	<10	0.68	1419	22	0.02	3	933	14	0.56	<5	5	123	<5	0.01	<10	<10	39	<10	61	2
8V2690RA/RJ	HL08-19	84781	32.77	34.77	2.00	0.04	0.6	0.99	54	178	<0.5	<5	2.41	1	9	66	26	2.76	<1	0.19	<10	0.47	970	8	0.01	2	765	34	0.47	<5	3	50	<5	0.01	<10	<10	35	<10	60	2
8V2690RA/RJ	HL08-19	84782	34.77	36.77	2.00	0.06	0.3	0.97	42	64	<0.5	<5	2.50	1	8	80	24	2.76	<1	0.18	<10	0.50	1008	5	0.01	3	684	8	0.48	<5	3	43	<5	0.01	<10	<10	35	<10	40	2
8V2690RA/RJ	HL08-19	84783	36.77	38.77	2.00	0.06	0.2	1.18	37	81	<0.5	<5	2.58	1	9	55	15	3.00	<1	0.20	<10	0.62	1066	2	0.02	1	852	48	0.36	<5	3	77	<5	0.03	<10	<10	41	<10	52	2
8V2690RA/RJ	HL08-19	84784	38.77	40.77	2.00	0.05	0.1	1.20	91	62	<0.5	<5	1.72	1	10	66	17	3.25	<1	0.19	<10	0.66	969	3	0.01	2	883	9	0.61	<5	3	58	<5	0.01	<10	<10	41	<10	56	2
8V2690RA/RJ	HL08-19	84785	40.77	42.68	1.91	0.03	0.2	1.24	37	70	<0.5	<5	1.47	<1	11	51	21	3.27	<1	0.21	<10	0.62	873	4	0.01	1	1046	9	0.35	<5	3	41	<5	0.01	<10	<10	43	<10	58	2
8V2690RA/RJ	HL08-19	84786	42.68	44.09	1.41	0.20	2.3	0.93	184	64	<0.5	<5	2.72	5	8	51	46	4.05	<1	0.19	<10	0.49	1224	5	0.01	2	676	601	2.47	<5	2	59	<5	0.01	<10	<10	33	<10	313	2
8V2690RA/RJ	HL08-19	84787	44.09	44.79	0.70	0.12	1.5	0.70	49	51	<0.5	<5	11.29	1	7	34	24	2.31	<1	0.12	<10	0.34	3331	3	0.01	1	528	16	0.90	<5	4	208	<5	0.01	<10	<10	30	<10	58	1
8V2690RA/RJ	HL08-19	84788	44.79	47.55	2.76	0.05	0.3	1.06	37	63	<0.5	<5	3.77	1	10	50	25	3.28	<1	0.21	<10	0.62	1420	3	0.01	1	883	14	0.52	<5	4	141	<5	0.01	<10	<10	42	<10	73	2
8V2690RA/RJ	HL08-19	84789	47.55	48.05	0.50	0.36	1.2	1.21	188	80	<0.5	<5	4.80	16	11	38	98	4.81	<1	0.18	<10	0.57	1438	3	0.01	1	767	33	2.72	<5	3	108	<5	0.01	<10	<10	49	18	1373	2
8V2690RA/RJ	HL08-19	84790	48.05	50.05	2.00	0.10	0.6	1.22	76	85	<0.5	<5	2.91	1	11	41	32	3.46	<1	0.25	<10	0.57	1744	5	0.01	2	884	60	0.99	<5	3	88	<5	0.02	<10	<10	38	<10	95	3
8V2690RA/RJ	HL08-19	84791	50.05	52.05	2.00	0.03	0.7	1.16	61	75	<0.5	<5	3.68	1	9	32	23	3.12	<1	0.19	<10	0.63	1708	2	0.01	1	869	40	0.77	<5	3	106	<5	0.02	<10	<10	38	<10	119	2
8V2690RA/RJ	HL08-19	84792	52.05	54.05	2.00	0.07	0.8	1.08	89	70	<0.5	<5	2.61	1	9	50	15	3.35	<1	0.21	<10	0.61	1291	2	0.01	2	865	30	1.33	<5	3	74	<5	0.01	<10	<10	38	<10	55	2
8V2690RA/RJ	HL08-19	84793	54.05	56.05	2.00	0.05	0.3	1.11	45	66	<0.5	<5	2.40	1	8	39	13	3.19	<1	0.20	<10	0.63	1109	2	0.01	1	909	8	0.85	<5	3	75	<5	0.01	<10	<10	40	<10	63	2
8V2698RA/RJ	HL08-19	84794	56.06	58.05	1.99	0.03	1.1	1.26	37	118	<0.5	<5	2.31	1	10	87	27	3.31	<1	0.26	<10	0.64	1146	4	0.01	3	924	77	0.64	<5	3	70	<5	0.01	<10	<10	45	<10	119	2
8V2698RA/RJ	HL08-19	84795	58.05	60.12	2.07	0.03	0.8	1.26	35	135	<0.5	<5	3.87	1	8	70	13	3.25	<1	0.26	<10	0.65	1346	7	0.02	2	961	21	0.65	<5	4	118	<5	0.01	<10	<10	45	<10	99	2
8V2698RA/RJ	HL08-19	84796	60.12	61.12	1.00	0.28	9.1	0.85	363	69	<0.5	<5	2.65	38	9	57	186	4.59	<1	0.13	<10	0.58	1656	2	0.01	2	602	2913	3.78	<5	2	52	<5	0.01	<10	<10	26	49	4120	2
8V2698RA/RJ	HL08-19	84797	61.12	62.12	1.00	0.57	10.3	1.01	653	56	<0.5	<5	0.99	45	10	77	116	6.90	<1	0.15	<10	0.74	1781	17	0.01	3	701	753	>5.00	<5	2	34	<5	0.01	<10	<10	34	55	4792	3
8V2698RA/RJ	HL08-19	84798	62.12	63.12	1.00	0.18	2.7	2.07	253	104	<0.5	<5	3.02	6	13	36	131	6.35	<1	0.19	<10	1.39	3343	17	0.01	2	1156	164	2.58	<5	4	123	<5	0.02	<10	<10	79	<10	388	3
8V2698RA/RJ	HL08-19	84799	63.12	64.12	1.00	0.11	4.1	1.05	265	132	<0.5	<5	4.06	5	14	47	213	4.92	<1	0.32	<10	1.02	3016	45	0.01	2	1254	69	2.07	<5	4	280	<5	0.01	<10	<10	44	<10	225	2
8V2698RA/RJ	HL08-19	84800	Std	PM1112		1.02	220.4	0.85	2288	103	<0.5	<5	4.40	38	66	22	2353	3.13	<1	0.09	<10	0.25	954	150	0.05	25	1048	421	0.72	420	2	152	<5	0.04	<10	<10	23	26	351	8
8V2698RA/RJ	HL08-19	84801	64.12	65.12	1.00	0.06	2.9	1.27	74	187	<0.5	<5	4.09	2	18	19	147	5.03	<1	0.64	<10	0.93	2402	22	0.01	2	1440	24	0.77	<5	5	256	<5	0.07	<10	<10	42	<10	158	2
8V2698RA/RJ	HL08-19	84802	65.12	66.12	1.00	0.11	2.7	1.63	94	139	<0.5	<5	5.17	2	17	23	95	5.61	<1	0.46	<10	1.16	3446	30	0.01	3	1530	73	1.59	<5	6	267	<5	0.03	<10	<10	59	<10	179	3
8V2698RA/RJ	HL08-19	84803	66.12	67.12	1.00	0.24	19.4	1.38	365	94	<0.5	<5	7.27	18	15	12	132	5.60	<1	0.25	<10	0.90	3742	12	0.01	2	1476	1958	4.65	<5	4	189	<5	0.01	<10	<10	76	24	1988	3
8V2698RA/RJ	HL08-19	84804	67.12	68.12	1.00	0.23	11.6	0.88	492	100	<0.5	<5	9.15	35	14	40	127	6.30	<1	0.21	<10	0.53	4652	16	0.01	3	1082	2901	>5.00	<5	3	247	<5	0.01	<10	<10	49	54	4298	3
8V2698RA/RJ	HL08-19	84805	68.12	69.50	1.38	0.62	6.1	1.04	196	124	<0.5	<5	4.61	6	12	43	116	4.32	<1	0.22	<10	0.65	3212	15	0.01	3	1143	267	3.35	<5	3	85	<5	0.03	<10	<10	50	<10	627	2
8V2698RA/RJ	HL08-19	84806	69.50	70.00	0.50	<0.01	<0.1	1.08	<5	237	<0.5	<5	2.36	<1	10	60	3	2.21	<1	0.31	15	0.66	720	<2	0.04	5	910	29	0.23	<5	3	65	<5	0.01	<10	<10	32	<10	67	11
8V2698RA/RJ	HL08-19	84807	78.48	7																																				

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																												
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm	
8V2698RA/RJ	HL08-20	84848	36.85	38.67	1.82	0.05	<0.1	1.20	35	73	<0.5	<5	1.88	<1	8	77	10	3.08	<1	0.23	<10	0.62	820	<2	0.02	2	994	9	0.42	<5	3	62	<0.01	<10	<10	37	<10	53	2		
8V2698RA/RJ	HL08-20	84849	36.67	40.67	2.00	0.08	0.6	1.31	63	66	<0.5	<5	2.47	<1	9	67	25	3.33	<1	0.22	<10	0.70	1345	5	0.01	2	900	10	0.68	<5	3	85	<0.01	<10	<10	42	<10	58	2		
8V2698RA/RJ	HL08-20	84850	Blank	Blank	Blank	0.01	<0.1	0.99	<5	235	0.8	<5	0.49	<1	8	125	<1	2.02	<1	0.49	<10	0.58	566	<2	0.08	6	785	5	<0.01	<5	2	54	0.15	<10	<10	38	<10	48	2		
8V2698RA/RJ	HL08-20	84851	40.67	42.67	2.00	0.10	0.3	1.51	57	84	<0.5	<5	2.35	1	12	66	21	3.81	<1	0.25	<10	0.92	1355	4	0.01	4	909	9	0.95	<5	4	106	<0.01	<10	<10	54	<10	92	2		
8V2698RA/RJ	HL08-20	84852	42.67	44.67	2.00	0.07	0.5	1.21	65	83	<0.5	<5	4.22	1	11	57	29	3.19	<1	0.24	<10	0.62	1711	3	0.01	2	941	13	0.86	<5	3	114	<0.01	<10	<10	42	<10	71	2		
8V2698RA/RJ	HL08-20	84853	44.67	46.67	2.00	0.11	0.6	1.30	38	68	<0.5	<5	3.63	1	11	53	69	3.39	<1	0.24	<10	0.59	1586	4	0.01	2	966	33	0.56	<5	3	101	0.01	<10	<10	56	<10	181	2		
8V2698RA/RJ	HL08-20	84854	46.67	48.67	2.00	0.05	0.4	1.09	48	73	<0.5	<5	2.85	<1	8	73	11	3.02	<1	0.25	<10	0.64	1392	2	0.01	2	804	11	0.65	<5	3	98	<0.01	<10	<10	31	<10	70	2		
8V2698RA/RJ	HL08-20	84855	48.67	50.04	1.37	0.06	1.1	0.82	78	66	<0.5	<5	6.40	1	9	57	16	2.98	<1	0.25	<10	0.57	2294	4	0.01	2	858	11	1.04	<5	3	223	<0.01	<10	<10	22	<10	94	2		
8V2698RA/RJ	HL08-20	84856	50.04	51.15	1.11	0.07	0.7	1.01	73	72	<0.5	<5	1.48	1	8	87	13	3.05	<1	0.21	<10	0.55	1136	2	0.01	2	685	8	0.95	<5	2	45	<0.01	<10	<10	32	<10	68	2		
8V2698RA/RJ	HL08-20	84857	51.15	52.98	1.83	0.11	1.5	0.73	94	72	<0.5	<5	2.49	2	6	105	23	2.52	<1	0.17	<10	0.43	1382	4	0.01	3	469	53	1.09	<5	2	68	<0.01	<10	<10	22	<10	89	1		
8V2698RA/RJ	HL08-20	84858	52.98	53.98	1.00	0.26	4.9	1.66	320	95	<0.5	<5	0.55	17	13	61	73	6.89	<1	0.17	<10	1.26	1981	6	0.01	2	972	1323	4.44	<5	3	18	<0.01	<10	<10	68	14	1655	3		
8V2698RA/RJ	HL08-20	84859	53.98	54.95	0.97	0.35	9.8	0.67	525	53	<0.5	<5	2.30	87	10	75	234	7.70	<1	0.13	<10	0.49	1661	6	0.01	1	704	3601	>5.00	<5	1	44	<0.01	<10	<10	28	84	9899	3		
8V2698RA/RJ	HL08-20	84860	54.95	56.48	1.53	0.20	10.0	1.03	265	116	<0.5	<5	1.37	42	10	92	212	5.33	<1	0.13	<10	0.76	2323	4	0.01	2	687	4722	4.16	<5	2	45	<0.01	<10	<10	54	41	5032	2		
8V2698RA/RJ	HL08-20	84861	56.48	58.03	1.55	0.34	27.7	1.11	650	50	<0.5	<5	2.42	73	15	53	1777	9.73	<1	0.15	<10	0.78	2089	<2	0.01	3	886	2217	>5.00	<5	2	66	<0.01	<10	<10	47	57	7318	4		
8V2698RA/RJ	HL08-20	84862	58.03	59.30	1.27	0.91	29.8	0.59	1371	35	<0.5	<5	2.62	148	11	84	2061	13.53	<1	0.09	<10	0.45	1535	<2	0.01	1	513	3994	>5.00	<5	1	56	<0.01	<10	<10	15	145	15900	5		
8V2698RA/RJ	HL08-20	84863	59.30	60.36	1.06	0.78	9.5	1.44	994	54	<0.5	<5	1.54	61	11	83	329	10.96	<1	0.11	<10	1.00	2026	6	0.01	2	556	1695	>5.00	<5	2	32	<0.01	<10	<10	11	34	46	5740	4	
8V2698RA/RJ	HL08-20	84864	60.36	61.32	0.96	0.58	5.2	2.26	523	64	<0.5	<5	0.33	57	11	64	160	10.23	<1	0.18	<10	1.64	2503	10	0.01	2	777	887	>5.00	<5	3	11	<0.01	<10	<10	14	49	48	6051	4	
8V2698RA/RJ	HL08-20	84865	61.32	62.48	1.16	0.23	5.7	1.61	226	76	<0.5	<5	1.03	6	8	85	136	6.57	<1	0.18	<10	1.21	2323	5	0.01	2	734	3599	4.14	<5	3	36	<0.01	<10	<10	48	<10	332	2		
8V2698RA/RJ	HL08-20	84866	62.48	64.08	1.60	0.16	4.5	1.26	200	95	<0.5	<5	2.20	12	12	85	141	6.00	<1	0.27	<10	0.75	1856	9	0.01	4	823	1808	>5.00	<5	3	55	<5	<0.01	<10	<10	44	12	1381	3	
8V2698RA/RJ	HL08-20	84867	64.08	64.68	0.60	0.02	<0.1	1.21	<5	859	0.5	14	2.42	<1	9	79	6	2.31	<1	0.42	<10	0.67	610	2	0.05	6	812	60	0.37	<5	3	111	<5	<0.01	<10	<10	33	27	94	7	
8V2698RA/RJ	HL08-20	84868	75.14	76.35	1.21	0.06	2.0	0.57	78	169	<0.5	<5	5.40	9	12	113	111	4.07	<1	0.33	<10	0.60	1644	6	0.01	3	765	156	2.27	<5	3	171	<5	<0.01	<10	<10	13	<10	1035	2	
8V2698RA/RJ	HL08-20	84869	76.35	77.28	0.93	0.27	2.2	0.76	182	125	<0.5	<5	2.28	14	13	162	57	5.53	<1	0.34	<10	0.74	1764	7	0.01	6	797	352	3.90	<5	3	128	<5	<0.01	<10	<10	31	24	1347	3	
8V2698RA/RJ	HL08-20	84870	77.28	79.28	2.00	0.08	2.7	0.98	172	134	<0.5	<5	3.49	9	11	77	105	4.38	<1	0.24	<10	0.69	2346	13	0.01	3	822	331	2.60	<5	3	96	<5	<0.01	<10	<10	52	<10	719	2	
8V2698RA/RJ	HL08-20	84871	79.28	81.28	2.00	0.05	1.5	1.36	131	141	<0.5	<5	2.11	4	11	146	77	4.13	<1	0.28	<10	0.80	2096	8	0.01	4	877	77	1.63	<5	4	51	<5	<0.01	<10	<10	58	11	311	2	
8V2698RA/RJ	HL08-20	84872	81.28	82.18	0.90	0.06	4.5	1.39	137	108	<0.5	<5	5.42	10	12	75	242	4.42	<1	0.25	<10	0.77	2737	8	0.01	3	914	613	2.09	<5	4	79	<5	<0.01	<10	<10	59	<10	1040	2	
8V2698RA/RJ	HL08-20	84873	82.18	83.42	1.24	0.28	10.5	1.21	518	60	<0.5	<5	0.96	36	17	188	362	7.40	<1	0.26	<10	0.78	1837	19	0.01	6	951	2196	>5.00	<5	3	24	<5	<0.01	<10	<10	57	34	3522	3	
8V2698RA/RJ	HL08-20	84874	83.42	84.42	1.00	0.55	6.7	1.19	707	60	<0.5	<5	2.63	49	15	88	145	8.20	<1	0.15	<10	0.85	2259	11	0.01	3	731	1215	>5.00	<5	3	41	<5	<0.01	<10	<10	50	34	4383	3	
8V2698RA/RJ	HL08-20	84875	Std	PM1110	Blank	1.83	190.0	0.99	212	239	0.5	90	6.12	6	19	26	3787	4.06	4	0.18	<10	0.21	7255	64	0.03	37	677	250	1.60	216	2	200	<5	0.07	<10	<10	26	17	285	11	
8V2698RA/RJ	HL08-20	84876	84.42	85.47	1.05	0.27	18.2	0.62	404	62	<0.5	<5	3.94	122	10	185	890	6.72	<1	0.18	<10	0.39	2169	56	0.01	5	539	7532	>5.00	<5	8	1	62	<5	<0.01	<10	<10	26	127	13400	3
8V2698RA/RJ	HL08-20	84877	85.47	86.47	1.00	0.30	7.0	1.49	567	55	<0.5	<5	4.38	66	14	66	129	9.66	<1	0.19	<10	1.07	3089	9	0.01	2	849	2787	>5.00	<5	3	75	<5	0.02	<10	<10	59	51	6416	4	
8V2698RA/RJ	HL08-20	84878	86.47	88.47	2.00	0.08	2.8																																		

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																										
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V2698RA/RJ	HL08-21	84917	52.00	54.39	2.39	0.03	0.3	0.92	34	75	<0.5	<5	4.41	<1	7	84	16	2.44	<1	0.21	<10	0.49	1566	4	0.01	2	708	6	0.54	<5	2	134	<0.01	<10	<10	28	<10	38	2	
8V2698RA/RJ	HL08-21	84918	54.39	56.39	2.00	0.08	0.2	1.19	57	76	<0.5	<5	3.33	<1	7	70	18	2.91	<1	0.19	<10	0.69	1333	4	0.02	2	782	7	0.35	<5	3	137	<0.01	<10	<10	39	<10	47	2	
8V2698RA/RJ	HL08-21	84919	56.39	58.39	2.00	0.01	<0.1	1.15	19	66	<0.5	<5	2.47	<1	7	82	13	2.84	<1	0.16	<10	0.65	962	2	0.02	1	738	6	0.42	<5	3	82	0.01	<10	<10	40	<10	46	2	
8V2698RA/RJ	HL08-21	84920	58.39	60.37	1.98	0.05	0.4	0.77	52	413	<0.5	<5	4.19	<1	6	82	12	2.61	<1	0.20	<10	0.46	1504	6	0.01	2	672	12	0.74	<5	3	213	<0.01	<10	<10	17	<10	44	2	
8V2698RA/RJ	HL08-21	84921	60.37	62.37	2.00	0.10	1.0	0.64	74	293	<0.5	<5	2.90	2	8	81	23	3.17	<1	0.23	<10	0.50	1518	8	0.01	2	798	206	1.03	<5	3	198	<0.01	<10	<10	10	<10	208	2	
8V2698RA/RJ	HL08-21	84922	62.37	63.52	1.15	0.06	1.0	0.99	59	370	<0.5	<5	5.43	1	8	61	18	2.82	<1	0.25	<10	0.53	1767	5	0.01	2	778	14	0.83	<5	3	374	<0.01	<10	<10	14	<10	87	2	
8V2698RA/RJ	HL08-21	84923	63.52	65.52	2.00	0.05	1.4	1.30	21	260	<0.5	<5	3.41	<1	9	65	131	3.03	<1	0.27	<10	0.57	1436	4	0.01	2	931	8	0.30	<5	2	154	<0.01	<10	<10	33	<10	149	2	
8V2698RA/RJ	HL08-21	84924	65.52	67.43	1.91	0.43	2.0	1.38	26	114	<0.5	<5	4.17	<1	9	45	204	3.20	<1	0.29	<10	0.54	1608	8	0.01	2	1034	16	0.40	<5	2	181	<0.01	<10	<10	39	<10	98	2	
8V2698RA/RJ	HL08-21	84925	Std	PM1116		0.07	755.9	0.85	470	195	<0.5	98	0.47	15	7	246	6392	2.09	5	0.28	<10	0.50	291	486	0.08	7	526	783	1.03	1264	2	77	0.05	<10	<10	27	<10	782	2	
8V2698RA/RJ	HL08-21	84926	67.43	69.43	2.00	0.09	2.9	1.27	51	121	<0.5	<5	3.48	1	9	45	115	3.29	<1	0.28	<10	0.56	1715	10	0.01	2	942	53	0.72	<5	2	117	<0.01	<10	<10	35	<10	89	2	
8V2698RA/RJ	HL08-21	84927	69.43	71.43	2.00	0.03	3.8	0.89	38	113	<0.5	<5	2.80	<1	9	85	75	2.82	<1	0.24	<10	0.41	1228	21	0.01	2	777	19	0.75	6	2	123	<0.01	<10	<10	30	<10	50	2	
8V2698RA/RJ	HL08-21	84928	71.43	73.28	1.85	0.96	2.5	1.43	210	162	<0.5	<5	3.52	4	15	43	84	4.72	<1	0.21	<10	1.02	1760	6	0.01	1	1056	100	1.74	<5	4	154	<0.01	<10	<10	68	<10	297	2	
8V2698RA/RJ	HL08-21	84929	73.28	74.66	1.38	0.27	0.8	1.66	38	74	<0.5	<5	2.89	<1	14	51	59	3.87	<1	0.25	<10	1.14	1656	5	0.01	1	1096	19	0.48	<5	4	148	<0.01	<10	<10	65	<10	94	2	
8V2698RA/RJ	HL08-21	84930	74.66	75.81	1.15	0.05	0.9	0.69	40	68	<0.5	<5	3.66	<1	10	59	26	3.34	<1	0.29	<10	0.88	1660	15	0.01	2	836	21	0.74	<5	4	187	<0.01	<10	<10	20	<10	81	2	
8V2698RA/RJ	HL08-21	84931	75.81	77.81	2.00	0.06	0.7	1.19	37	91	<0.5	<5	2.92	<1	9	80	28	2.93	<1	0.24	<10	0.69	1439	9	0.01	2	873	13	0.73	<5	3	152	<0.01	<10	<10	38	<10	105	2	
8V2698RA/RJ	HL08-21	84932	77.81	79.81	2.00	0.11	0.8	1.20	96	85	<0.5	<5	2.25	1	9	78	40	3.47	<1	0.22	<10	0.75	1497	6	0.01	2	874	22	1.44	<5	3	111	<0.01	<10	<10	39	<10	92	2	
8V2698RA/RJ	HL08-21	84933	79.81	81.81	2.00	0.06	1.3	1.02	96	89	<0.5	<5	2.73	2	9	50	34	3.37	<1	0.26	<10	0.55	1791	4	0.01	1	976	76	1.76	<5	2	119	<0.01	<10	<10	25	<10	216	3	
8V2698RA/RJ	HL08-21	84934	81.81	83.92	2.11	0.08	5.8	0.76	95	114	<0.5	<5	2.76	13	9	52	162	3.42	<1	0.33	<10	0.57	1684	3	0.01	2	948	1222	1.77	<5	3	148	<0.01	<10	<10	15	15	1452	2	
8V2698RA/RJ	HL08-21	84935	83.92	85.56	1.64	0.03	1.0	0.56	66	64	<0.5	<5	2.77	1	7	84	42	2.38	<1	0.20	<10	0.46	1721	4	0.01	2	660	60	1.07	<5	2	84	<0.01	<10	<10	15	<10	106	1	
8V2698RA/RJ	HL08-21	84936	85.56	87.56	2.00	0.34	4.7	0.47	165	68	<0.5	<5	5.85	8	7	64	120	3.19	<1	0.16	<10	0.39	2496	4	0.01	2	713	570	2.71	<5	2	251	<0.01	<10	<10	15	<10	713	2	
8V2698RA/RJ	HL08-21	84937	87.56	88.56	1.00	0.13	0.1	0.30	108	69	<0.5	<5	4.45	8	5	135	33	2.36	<1	0.15	<10	0.17	1570	4	0.01	3	279	645	2.03	<5	1	135	<5	<0.01	<10	<10	8	<10	870	1
8V2698RA/RJ	HL08-21	84938	88.56	89.56	1.00	0.13	7.3	0.43	165	114	<0.5	<5	3.39	30	10	107	170	4.44	<1	0.22	<10	0.58	2246	10	0.01	2	739	3807	3.70	6	3	191	<5	<0.01	<10	<10	18	24	3129	2
8V2698RA/RJ	HL08-21	84939	89.56	90.78	1.22	0.17	3.7	0.37	184	85	<0.5	<5	8.50	11	8	79	91	4.01	<1	0.16	<10	0.38	3584	4	0.01	2	613	548	4.00	<5	2	349	<5	<0.01	<10	<10	13	<10	906	2
8V2698RA/RJ	HL08-21	84940	90.78	92.43	1.65	0.12	5.7	0.49	185	104	<0.5	<5	5.47	18	9	103	91	4.11	<1	0.20	<10	0.46	2459	7	0.01	2	721	1837	3.81	<5	2	227	<5	<0.01	<10	<10	17	15	1862	2
8V2698RA/RJ	HL08-21	84941	92.43	94.12	1.69	0.09	2.6	0.91	141	230	<0.5	<5	2.73	10	8	105	79	4.03	<1	0.26	<10	0.81	2309	2	0.01	2	858	572	1.96	<5	4	159	<5	<0.01	<10	<10	29	<10	1022	2
8V2698RA/RJ	HL08-21	84942	94.12	96.06	1.94	0.10	3.0	0.70	123	142	<0.5	<5	3.10	14	9	113	97	3.93	<1	0.27	<10	0.59	2155	27	0.01	2	811	699	2.54	<5	3	150	<5	<0.01	<10	<10	21	12	1576	2
8V2698RA/RJ	HL08-21	84943	96.06	97.84	1.78	0.15	12.2	0.53	463	72	<0.5	<5	4.60	78	8	106	590	5.88	<1	0.15	<10	0.34	2101	5	0.01	2	660	7627	>5.00	<5	2	131	<5	<0.01	<10	<10	28	73	9106	2
8V2698RA/RJ	HL08-21	84944	97.84	99.07	1.23	0.22	5.4	0.58	276	93	<0.5	<5	5.30	20	12	93	268	4.78	<1	0.16	<10	0.42	2501	28	0.01	3	725	1534	4.61	<5	3	177	<5	<0.01	<10	<10	45	16	2023	2
8V2698RA/RJ	HL08-21	84945	99.07	100.40	1.33	0.17	5.4	0.84	296	120	<0.5	<5	5.82	29	13	79	316	4.76	<1	0.15	<10	0.58	2185	36	0.01	4	862	1253	4.18	<5	3	165	<5	<0.01	<10	<10	63	24	3081	2
8V2698RA/RJ	HL08-21	84946	100.40	101.79	1.39	0.22	4.2	0.52	212	72	<0.5	<5	11.90	19	8	81	177	3.15	<1	0.09	<10	0.37	3498	44	0.01	3	384	764	2.55	<5	3	286	<5	<0.01	<10	<10	36	14	1806	1
8V2698RA/RJ	HL08-21	84947	101.79	103.79	2.00	0.10	2.3	1.07	148	114	<0.5	<5	4.1																											

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V2768RA/RJ	HL08-22	84988	32.20	33.00	0.80	0.08	1.8	0.64	71	141	<0.5	<5	1.48	4	16	45	107	5.20	<1	0.42	<10	0.96	2054	7	0.01	2	1342	49	1.53	<5	4	121	<5	<0.01	<10	<10	21	<10	434	2
8V2768RA/RJ	HL08-22	84989	33.00	34.50	1.50	0.15	3.1	1.39	203	154	<0.5	<5	1.40	8	17	114	123	5.18	<1	0.39	<10	0.99	2255	11	0.01	4	1147	686	1.85	<5	4	73	<5	<0.01	<10	<10	49	<10	782	2
8V2768RA/RJ	HL08-22	84990	34.50	36.05	1.55	0.37	5.6	1.20	500	87	<0.5	<5	1.13	39	15	93	140	6.96	<1	0.31	<10	1.03	2653	5	0.01	3	1103	9355	>5.00	<5	3	69	<5	<0.01	<10	<10	42	32	3981	3
8V2768RA/RJ	HL08-22	84991	36.05	37.00	0.95	0.16	17.9	0.94	631	38	<0.5	<5	2.34	180	10	159	379	9.31	<1	0.16	<10	0.89	2586	2	0.01	4	653	9900	>5.00	<5	2	76	<5	<0.01	<10	<10	30	193	20300	4
8V2768RA/RJ	HL08-22	84992	37.00	38.88	1.88	0.41	3.6	0.67	285	147	<0.5	<5	1.62	10	12	109	89	5.15	<1	0.26	<10	0.70	2746	8	0.01	4	919	419	2.58	<5	3	84	<5	<0.01	<10	<10	34	<10	895	2
8V2768RA/RJ	HL08-22	84993	38.88	40.76	1.88	0.09	4.3	0.91	204	127	<0.5	<5	3.17	6	12	147	98	4.21	<1	0.32	<10	0.72	2953	9	0.01	6	910	200	2.43	<5	3	141	<5	<0.01	<10	<10	38	<10	393	2
8V2768RA/RJ	HL08-22	84994	40.76	42.64	1.88	0.15	4.9	0.52	320	137	<0.5	<5	4.70	21	10	75	243	3.94	<1	0.24	<10	0.56	2933	7	0.01	4	817	1294	2.74	<5	2	188	<5	<0.01	<10	<10	23	19	2424	2
8V2768RA/RJ	HL08-22	84995	42.64	44.20	1.56	0.36	2.9	1.47	388	131	<0.5	<5	2.55	9	13	104	167	4.56	<1	0.27	<10	0.80	2492	5	0.01	6	858	129	2.00	<5	3	84	<5	<0.01	<10	<10	50	<10	270	2
8V2768RA/RJ	HL08-22	84996	44.20	44.82	0.62	0.11	2.5	1.37	212	162	<0.5	<5	2.32	5	13	60	135	4.36	<1	0.25	<10	0.69	2082	12	0.01	6	917	85	1.62	<5	3	65	<5	<0.01	<10	<10	50	<10	242	2
8V2768RA/RJ	HL08-22	84997	44.82	46.50	1.68	0.06	1.9	1.31	63	96	<0.5	<5	1.70	2	12	49	141	3.62	<1	0.20	<10	0.64	1741	2	0.01	4	875	25	0.87	<5	2	45	<5	<0.01	<10	<10	46	<10	218	2
8V2768RA/RJ	HL08-22	84998	46.50	48.10	1.60	0.10	2.6	1.33	69	91	<0.5	<5	3.00	2	10	49	195	3.58	<1	0.21	<10	0.70	2250	6	0.01	3	826	81	0.98	<5	2	125	<5	<0.01	<10	<10	43	<10	175	2
8V2768RA/RJ	HL08-22	84999	48.10	49.73	1.63	0.14	3.1	1.26	117	101	<0.5	<5	2.83	2	10	52	158	3.58	<1	0.19	<10	0.67	2201	7	0.01	3	781	42	1.05	<5	2	95	<5	<0.01	<10	<10	45	<10	139	2
8V2768RA/RJ	HL08-22	85000	Blank	Blank	<0.01	<0.1	0.99	<5	261	0.8	<5	0.47	<1	9	123	<1	2.08	<1	0.51	<10	0.58	604	<2	0.07	5	750	6	0.01	<5	2	52	5	0.13	<10	<10	41	<10	48	2	
8V2768RA/RJ	HL08-22	85001	49.73	50.91	1.18	0.14	4.3	0.72	110	94	<0.5	<5	3.39	4	6	47	131	2.77	<1	0.24	<10	0.33	1837	45	0.01	1	842	203	1.34	<5	2	117	<5	<0.01	<10	<10	20	<10	310	1
8V2768RA/RJ	HL08-22	85002	50.91	52.75	1.84	0.14	1.3	1.13	88	174	<0.5	<5	0.72	3	9	38	118	3.87	<1	0.25	<11	0.42	1465	5	0.01	1	1041	23	1.29	<5	2	17	<5	<0.01	<10	<10	43	<10	293	2
8V2768RA/RJ	HL08-22	85003	52.75	53.58	0.83	0.31	2.2	0.77	189	164	<0.5	<5	4.53	8	8	57	71	4.32	<1	0.22	<10	0.30	2581	16	0.01	2	865	74	2.59	<5	2	154	<5	<0.01	<10	<10	27	<10	505	2
8V2768RA/RJ	HL08-22	85004	53.58	55.20	1.62	0.04	0.2	1.26	16	149	<0.5	<5	2.79	1	7	40	4	3.04	<1	0.26	<10	0.64	1674	<2	0.01	1	876	8	0.37	<5	2	141	<5	<0.01	<10	<10	41	<10	109	3
8V2768RA/RJ	HL08-22	85005	55.20	56.80	1.60	0.11	1.9	1.18	70	156	<0.5	<5	3.17	22	7	52	58	3.18	<1	0.25	<10	0.68	1744	<2	0.01	1	824	836	1.04	<5	3	142	<5	<0.01	<10	<10	48	16	2004	2
8V2768RA/RJ	HL08-22	85006	56.80	58.40	1.60	0.03	0.2	1.19	19	94	<0.5	<5	3.16	<1	8	43	11	2.88	<1	0.24	<10	0.69	1557	<2	0.01	1	839	20	0.60	<5	3	108	<5	<0.01	<10	<10	49	<10	84	2
8V2768RA/RJ	HL08-22	85007	58.40	60.05	1.65	0.14	3.3	1.22	89	168	<0.5	<5	2.13	3	11	97	119	3.45	<1	0.39	<10	0.94	1286	8	0.02	39	868	156	1.74	<5	3	84	<5	0.01	<10	<10	45	<10	257	3
8V2768RA/RJ	HL08-22	85008	60.05	61.30	1.25	0.57	3.2	1.38	88	101	<0.5	<5	2.63	34	10	34	143	4.18	<1	0.18	<10	0.84	2293	12	0.01	1	776	1751	2.12	<5	2	78	<5	0.03	<10	<10	42	23	2880	2
8V2768RA/RJ	HL08-22	85009	61.30	62.58	1.28	0.06	2.5	0.91	48	109	<0.5	<5	4.23	3	8	24	126	2.35	<1	0.19	<10	0.44	2596	15	0.01	1	735	340	0.92	<5	2	113	<5	0.03	<10	<10	28	<10	397	1
8V2768RA/RJ	HL08-22	85010	62.58	64.50	1.92	0.02	0.2	1.02	17	78	<0.5	<5	2.64	<1	6	34	6	2.33	<1	0.23	<10	0.53	1314	<2	0.01	1	673	26	0.56	<5	2	104	<5	<0.01	<10	<10	34	<10	69	2
8V2768RA/RJ	HL08-22	85011	64.50	66.50	2.00	0.04	2.2	1.05	38	83	<0.5	<5	3.61	1	10	24	108	3.49	<1	0.25	<10	0.65	2520	5	0.01	1	899	22	1.39	<5	3	137	<5	<0.01	<10	<10	34	<10	110	2
8V2768RA/RJ	HL08-22	85012	66.50	68.50	2.00	0.03	2.0	1.14	29	71	<0.5	<5	2.93	1	9	29	121	3.09	<1	0.20	<10	0.60	2299	13	0.01	1	849	36	1.12	<5	2	103	<5	0.01	<10	<10	39	<10	114	2
8V2768RA/RJ	HL08-22	85013	68.50	70.50	2.00	0.04	0.5	1.08	10	240	<0.5	<5	2.88	<1	8	40	8	2.92	<1	0.29	<10	0.62	1983	<2	0.02	1	848	35	0.72	<5	2	105	<5	<0.01	<10	<10	30	<10	67	3
8V2768RA/RJ	HL08-22	85014	70.50	72.48	1.98	0.10	2.7	0.91	39	127	<0.5	<5	3.25	7	9	48	55	3.45	<1	0.33	<10	0.68	1907	2	0.01	1	919	1704	1.04	<5	3	150	<5	<0.01	<10	<10	27	<10	794	3
8V2768RA/RJ	HL08-22	85015	72.48	74.50	2.02	0.16	6.0	1.59	221	107	<0.5	<5	5.47	18	15	50	306	5.01	<1	0.18	<10	0.96	2606	13	0.01	6	1286	1330	2.40	<5	7	159	<5	0.04	<10	<10	91	14	1755	2
8V2768RA/RJ	HL08-22	85016	74.50	76.50	2.00	0.16	4.4	1.94	93	99	<0.5	<5	5.01	13	14	49	349	5.59	<1	0.17	<10	1.27	2803	23	0.01	5	1467	420	2.34	<5	8	144	<5	0.03	<10	<10	92	12	1366	2
8V2768RA/RJ	HL08-22	85017	76.50	78.52	2.02	0.09	5.3	2.18	93	113	<0.5	<5	6.64	9	16	40	434	5.80	<1	0.25	<10	1.76	3723	19	0.01	5	1449	552	1.72	<5	10	260	<5	0.02	<10	<10				

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V2768RA/RJ	HL08-23	85059	22.22	24.07	1.85	0.13	0.7	1.53	97	76	<0.5	<5	1.32	11	10	53	33	4.87	<1	0.15	<10	1.07	1755	6	0.01	1	783	476	1.70	<5	3	44	<5	0.01	<10	<10	50	12	1402	2
8V2768RA/RJ	HL08-23	85060	24.07	24.58	0.51	2.44	27.4	1.16	1181	26	<0.5	<9	0.42	181	7	69	129	12.38	<1	0.06	<10	1.00	1395	<2	0.01	<1	472	2990	>5.00	<5	1	12	<5	<0.01	<10	<10	21	165	3080	5
8V2768RA/RJ	HL08-23	85061	24.58	25.53	0.95	0.15	2.4	1.14	143	121	<0.5	<5	1.27	20	9	83	18	4.89	<1	0.15	<10	1.00	1791	10	0.01	1	650	1312	2.47	<5	3	62	<5	<0.01	<10	<10	33	19	2538	2
8V2768RA/RJ	HL08-23	85062	25.53	27.12	1.59	0.15	1.8	1.43	132	189	<0.5	<5	1.16	16	10	72	45	5.29	<1	0.19	<10	1.06	1810	6	0.01	2	817	1285	2.07	<5	3	48	<5	<0.01	<10	<10	41	16	2095	2
8V2768RA/RJ	HL08-23	85063	27.12	29.12	2.00	0.26	2.9	1.56	277	104	<0.5	<5	1.78	16	11	54	51	6.17	<1	0.20	<10	1.13	2030	4	0.01	1	833	951	3.38	<5	3	74	<5	<0.01	<10	<10	47	13	1574	3
8V2768RA/RJ	HL08-23	85064	29.12	30.88	1.76	0.25	2.8	1.77	270	111	<0.5	<5	1.49	28	16	76	132	6.51	<1	0.30	<10	1.08	2230	7	0.01	3	1239	666	3.85	<5	4	57	<5	<0.01	<10	<10	66	25	3333	3
8V2768RA/RJ	HL08-23	85065	30.88	31.88	1.00	0.15	3.0	2.09	219	126	<0.5	<5	1.03	20	18	48	115	6.66	<1	0.28	<10	1.49	2280	8	0.01	2	1439	1038	3.30	<5	4	31	<5	0.01	<10	11	85	18	2244	3
8V2768RA/RJ	HL08-23	85066	31.88	32.28	0.40	0.30	8.5	0.81	518	51	<0.5	<5	0.89	57	12	185	267	6.96	<1	0.24	<10	0.48	1374	9	0.01	5	962	3685	>5.00	<5	2	29	<5	0.01	<10	<10	37	55	7044	3
8V2768RA/RJ	HL08-23	85067	32.28	33.17	0.89	0.18	4.6	1.59	313	111	<0.5	<5	1.25	19	18	54	226	6.27	<1	0.26	<10	1.09	3030	8	0.01	2	1252	910	4.11	<5	4	37	<5	0.01	<10	11	69	16	1993	2
8V2768RA/RJ	HL08-23	85068	33.17	33.75	0.58	0.61	79.9	0.26	660	18	<0.5	<5	2.04	200	6	233	3396	12.16	<1	0.10	<10	0.35	1480	<2	0.01	4	453	5800	>5.00	52	<1	112	<5	<0.01	<10	<10	6	196	2230	5
8V2768RA/RJ	HL08-23	85069	33.75	34.87	1.12	0.27	5.4	1.05	243	111	<0.5	<5	2.57	15	13	81	175	5.96	<1	0.23	<10	0.80	2702	6	0.01	3	906	987	4.09	<5	3	89	<5	<0.01	<10	<10	40	11	1342	2
8V2768RA/RJ	HL08-23	85070	34.87	36.85	1.98	0.11	3.2	1.72	151	175	<0.5	<5	3.38	5	16	143	137	5.56	<1	0.36	<10	1.24	3490	5	0.01	6	1192	468	2.21	<5	4	138	<5	<0.01	<10	11	65	<10	389	2
8V2768RA/RJ	HL08-23	85071	36.85	38.25	2.00	0.07	3.5	1.61	176	122	<0.5	<5	3.14	4	17	58	185	5.18	<1	0.31	<10	1.16	3407	10	0.01	4	1238	96	1.88	<5	4	106	<5	<0.01	<10	11	67	<10	261	2
8V2768RA/RJ	HL08-23	85072	38.25	40.55	1.70	0.21	4.5	1.02	371	128	<0.5	<5	4.87	9	15	91	190	5.52	<1	0.31	<10	1.08	3622	4	0.01	4	1114	194	2.80	5	4	222	<5	<0.01	<10	<10	44	<10	371	2
8V2768RA/RJ	HL08-23	85073	40.55	42.28	1.73	0.31	3.3	1.46	176	109	<0.5	<5	4.52	5	15	47	190	5.07	<1	0.27	<10	1.02	3196	4	0.01	3	1168	110	2.36	<5	3	116	<5	<0.01	<10	<10	60	<10	409	2
8V2768RA/RJ	HL08-23	85074	42.28	43.47	1.19	0.11	6.3	0.73	129	84	<0.5	<5	6.00	5	9	185	34	3.36	<1	0.24	<10	0.46	3469	5	0.01	5	570	600	2.95	<5	1	164	<5	<0.01	<10	<10	25	<10	679	2
8V2768RA/RJ	HL08-23	85075	Std	PM922	6.34	2.9	2.31	629	248	1.2	169	11.68	13	53	170	502	7.41	9	0.27	17	0.47	1310	102	0.08	78	962	98	2.45	<5	5	151	<5	0.20	<10	<10	61	20	106	24	
8V2768RA/RJ	HL08-23	85076	43.47	44.59	1.12	0.12	4.1	1.86	134	205	<0.5	<5	1.75	4	16	148	182	5.60	<1	0.25	<10	1.35	3836	14	0.01	5	1135	388	1.89	<5	4	45	<5	0.01	<10	13	90	<10	561	2
8V2768RA/RJ	HL08-23	85077	44.59	46.18	1.59	0.22	3.0	1.74	151	81	<0.5	<5	5.44	5	15	52	175	5.07	<1	0.21	<10	1.16	3681	10	0.01	4	1059	163	1.98	<5	3	145	<5	<0.01	<10	<10	77	<10	413	2
8V2768RA/RJ	HL08-23	85078	46.18	47.99	1.81	0.12	2.6	1.88	130	123	<0.5	<5	3.88	4	17	67	160	5.91	<1	0.29	<10	1.23	3124	15	0.01	3	1276	259	2.02	<5	4	141	<5	<0.01	<10	<10	86	<10	404	2
8V2768RA/RJ	HL08-23	85079	47.99	48.45	0.46	0.31	9.5	0.53	176	108	<0.5	<5	10.50	15	11	45	208	4.18	<1	0.16	<10	0.29	3366	19	0.01	2	851	1147	3.82	<5	2	176	<5	<0.01	<10	<10	40	13	1633	2
8V2768RA/RJ	HL08-23	85080	48.45	49.29	0.84	0.09	3.1	1.68	92	159	<0.5	<5	3.83	5	16	111	289	5.61	<1	0.30	<10	0.93	2832	13	0.01	5	1121	208	2.49	<5	4	107	<5	<0.01	<10	<10	92	<10	736	2
8V2768RA/RJ	HL08-23	85081	49.29	51.30	2.01	0.02	0.2	1.43	51	157	<0.5	<5	3.26	1	8	57	10	3.41	<1	0.35	<10	0.82	1710	<2	0.02	2	934	22	0.61	<5	3	91	<5	<0.01	<10	<10	47	<10	92	3
8V2768RA/RJ	HL08-23	85082	51.30	53.30	2.00	0.01	<0.1	1.48	38	142	<0.5	<5	2.96	<1	9	84	8	3.43	<1	0.36	12	0.85	1551	<2	0.02	2	949	13	0.55	<5	3	85	<5	<0.01	<10	<10	56	<10	80	3
8V2768RA/RJ	HL08-23	85083	53.30	55.30	2.00	0.03	<0.1	1.42	36	130	<0.5	<5	2.90	<1	9	53	7	3.46	<1	0.35	12	0.84	1550	<2	0.02	2	956	11	0.66	<5	3	90	<5	<0.01	<10	<10	52	<10	77	3
8V2768RA/RJ	HL08-23	85084	55.30	57.30	2.00	0.03	0.9	1.38	57	140	<0.5	<5	5.21	8	8	86	7	3.41	<1	0.32	13	0.75	2275	<2	0.01	2	787	693	0.93	<5	3	119	<5	<0.01	<10	<10	45	<10	909	3
8V2768RA/RJ	HL08-23	85085	57.30	57.85	0.55	0.11	3.6	1.29	117	139	<0.5	<5	2.66	26	9	67	92	3.99	<1	0.27	<10	0.70	1833	<2	0.01	2	877	2293	1.69	<5	2	68	<5	0.01	<10	<10	55	21	2641	4
8V2768RA/RJ	HL08-23	85086	57.85	59.85	2.00	0.12	3.4	1.91	367	110	<0.5	<5	3.67	14	18	41	216	5.39	<1	0.22	<10	1.16	2943	12	0.01	2	1251	312	1.55	<5	4	78	<5	0.08	<10	<10	95	<10	959	2
8V2768RA/RJ	HL08-23	85087	59.85	61.85	2.00	0.28	5.8	1.75	2349	97	<0.5	<5	3.66	59	19	38	281	6.02	<1	0.18	<10	1.09	3374	9	0.01	3	1195	387	2.68	14	4	60	<5	0.06	<10	10	95	<10	1023	2
8V2768RA/RJ	HL08-23	85088	61.85	63.85	2.00	0.08	4.4	1.67	75	108	0.8	<5	3.34	3	19	39	215	4.59	<1	0.25	<10	0.92	2820	14	0.02	3	1362	168	1.45	<5	5	81	<5	0.12						

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																										
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V2699RA/RJ	HL08-24	85201	75.00	76.00	1.00	5.56	100.0	0.13	1309	25	<0.5	10	3.11	378	9	119	2247	14.20	<1	0.06	<10	0.43	2143	<2	<0.01	1	512	44800	>5.00	50	1	157	<5	<0.01	<10	<10	5	517	39100	6
8V2699RA/RJ	HL08-24	85202	76.00	77.00	1.00	1.51	15.1	0.35	1008	40	<0.5	7	3.11	186	6	118	270	8.02	<1	0.12	<10	0.57	2088	2	0.01	2	444	14700	>5.00	<5	1	125	<5	<0.01	<10	<10	9	271	17900	3
8V2699RA/RJ	HL08-24	85203	77.00	78.00	1.00	5.13	10.1	0.33	510	50	<0.5	5	2.72	56	8	199	97	6.08	<1	0.15	<10	0.79	2525	2	0.01	6	445	1435	>5.00	<5	1	129	<5	<0.01	<10	<10	8	71	5640	3
8V2699RA/RJ	HL08-24	85204	78.00	79.50	1.50	1.09	3.4	0.26	323	53	<0.5	<5	9.65	30	7	86	54	3.94	<1	0.12	<10	0.48	3010	3	0.01	4	498	358	3.26	<5	3	237	<5	<0.01	<10	<10	11	40	3064	2
8V2699RA/RJ	HL08-24	85205	79.50	80.00	0.50	0.39	20.5	0.29	447	30	<0.5	7	4.89	91	9	88	604	9.46	<1	0.05	<10	0.37	2491	<2	<0.01	4	364	15800	>5.00	<5	1	114	<5	<0.01	<10	<10	8	126	9621	4
8V2699RA/RJ	HL08-24	85206	80.00	80.50	0.50	0.87	29.8	0.24	800	38	<0.5	5	3.30	212	11	54	2175	11.64	<1	0.06	<10	0.62	2976	<2	<0.01	2	510	17200	>5.00	5	1	147	<5	<0.01	<10	<10	8	304	21800	5
8V2699RA/RJ	HL08-24	85207	80.50	81.15	0.65	0.92	35.2	0.24	869	30	<0.5	7	2.95	220	10	67	2402	12.67	<1	0.04	<10	0.38	2773	<2	<0.01	2	501	22500	>5.00	14	1	83	<5	<0.01	<10	<10	9	322	22600	5
8V2699RA/RJ	HL08-24	85208	81.15	82.10	0.95	0.42	40.4	0.12	483	27	<0.5	11	1.67	184	17	170	1139	10.49	<1	0.04	<10	0.32	1270	<2	0.01	4	335	12000	>5.00	6	<1	58	<5	<0.01	<10	<10	5	278	18200	4
8V2699RA/RJ	HL08-24	85209	82.10	83.00	0.90	0.85	32.3	0.61	817	21	<0.5	10	1.07	445	14	115	1299	12.67	<1	0.06	<10	0.82	1895	<2	0.01	2	441	17000	>5.00	<5	1	50	<5	<0.01	<10	<10	18	704	52000	6
8V2699RA/RJ	HL08-24	85210	83.00	84.40	1.40	0.28	3.4	0.36	264	65	<0.5	<5	2.45	27	9	137	95	5.17	<1	0.14	<10	0.48	1424	5	0.01	5	508	711	4.61	<5	1	95	<5	<0.01	<10	<10	11	37	3002	2
8V2699RA/RJ	HL08-24	85211	84.40	85.50	1.10	0.24	4.9	0.27	429	94	<0.5	<5	2.56	29	10	231	136	5.13	<1	0.22	<10	0.43	1427	13	0.01	7	618	1720	4.76	<5	1	107	<5	<0.01	<10	<10	7	37	2900	2
8V2699RA/RJ	HL08-24	85212	85.50	87.00	1.50	0.17	7.2	0.22	271	70	<0.5	<5	2.92	18	8	135	275	3.90	<1	0.12	<10	0.25	1454	8	0.01	4	438	895	3.38	<5	1	103	<5	<0.01	<10	<10	8	20	1617	2
8V2768RA/RJ	HL08-24	85213	87.00	88.10	1.10	0.20	3.3	0.28	184	81	<0.5	<5	4.05	32	8	55	82	3.26	<1	0.17	<10	0.37	1611	2	0.01	2	520	896	3.11	<5	2	180	<5	<0.01	<10	<10	11	24	3231	1
8V2768RA/RJ	HL08-24	85214	88.10	89.63	1.53	0.13	1.6	0.60	77	97	<0.5	<5	4.82	5	11	74	95	3.19	<1	0.18	<10	0.43	1872	9	0.01	6	662	239	1.13	<5	4	199	<5	<0.01	<10	<10	28	10	490	1
8V2768RA/RJ	HL08-24	85215	89.63	91.50	1.87	0.12	3.0	0.29	127	104	<0.5	<5	3.30	23	16	64	185	3.69	<1	0.25	<10	0.57	1653	14	0.01	5	847	262	2.21	<5	3	195	<5	<0.01	<10	<10	8	16	2150	1
8V2768RA/RJ	HL08-24	85216	91.50	93.00	1.50	0.10	2.0	0.46	137	104	<0.5	<5	4.27	7	13	34	151	4.34	<1	0.26	<10	0.91	2146	9	0.01	2	885	139	1.58	<5	4	253	<5	<0.01	<10	<10	16	10	487	2
8V2768RA/RJ	HL08-24	85217	93.00	94.50	1.50	0.08	2.0	0.29	116	189	<0.5	<5	5.64	6	10	53	128	3.56	<1	0.22	<10	0.74	2507	5	0.01	3	688	171	1.76	<5	3	390	<5	<0.01	<10	<10	7	<10	467	1
8V2768RA/RJ	HL08-24	85218	94.50	96.00	1.50	0.17	2.4	0.43	169	109	<0.5	<5	6.72	7	10	55	67	3.40	<1	0.20	<10	0.36	2036	7	0.01	3	552	242	2.51	<5	3	362	<5	<0.01	<10	<10	8	<10	439	1
8V2768RA/RJ	HL08-24	85219	96.00	97.82	1.82	0.15	2.9	0.20	156	86	<0.5	<5	8.22	12	6	66	75	2.76	<1	0.15	<10	0.26	2135	4	0.01	2	448	640	2.57	<5	2	412	<5	<0.01	<10	<10	6	<10	1031	1
8V2768RA/RJ	HL08-24	85220	97.82	99.50	1.68	0.04	1.5	1.16	40	132	<0.5	<5	10.18	4	11	46	126	3.32	<1	0.16	<10	0.83	2473	7	0.01	4	749	109	1.10	<5	5	274	<5	<0.01	<10	<10	48	<10	416	1
8V2768RA/RJ	HL08-24	85221	99.50	101.00	1.50	0.06	1.8	0.85	62	162	<0.5	<5	8.77	4	18	46	155	3.18	<1	0.17	<10	0.70	2196	4	0.01	3	666	127	1.56	<5	5	217	<5	<0.01	<10	<10	36	<10	355	1
8V2768RA/RJ	HL08-24	85222	101.00	102.20	1.20	0.06	1.0	1.01	80	73	<0.5	<5	8.38	3	8	35	23	3.36	<1	0.11	<10	0.80	2492	6	0.01	2	561	90	1.41	<5	4	257	<5	<0.01	<10	<10	40	<10	277	1
8V2768RA/RJ	HL08-24	85223	102.20	103.40	1.20	0.12	0.5	0.61	61	11	<0.5	<5	1.74	3	5	5	15	2.40	<1	0.02	<10	0.59	1755	5	<0.01	<1	219	52	1.09	<5	1	34	<5	<0.01	<10	<10	20	<10	254	1
8V2768RA/RJ	HL08-24	85224	103.40	104.70	1.30	0.37	6.8	0.72	168	86	<0.5	<5	2.59	21	14	91	241	4.28	<1	0.24	<10	1.05	1585	15	0.02	47	671	1394	3.07	5	3	115	<5	0.01	<10	<10	31	20	2213	2
8V2768RA/RJ	HL08-24	85225	Std	PM 111.02		1.31	209.3	0.95	1574	118	<0.5	46	4.56	37	55	75	2007	3.08	1	0.16	<10	0.27	986	104	0.06	23	733	378	0.68	294	2	142	<5	0.04	<10	<10	23	14	311	6
8V2768RA/RJ	HL08-24	85226	104.70	106.00	1.30	0.52	3.8	1.19	277	42	<0.5	<5	3.07	48	9	93	68	5.85	<1	0.11	<10	0.88	1757	<2	<0.01	3	701	1139	0.50	<5	2	192	<5	<0.01	<10	<10	5	40	5012	2
8V2768RA/RJ	HL08-24	85227	106.00	107.06	1.06	0.12	2.8	0.72	164	84	<0.5	<5	1.75	8	8	101	33	3.53	<1	0.14	<10	0.83	1537	7	0.01	3	522	290	1.43	<5	3	91	<5	<0.01	<10	<10	25	<10	584	2
8V2768RA/RJ	HL08-24	85228	107.06	108.30	1.24	0.02	1.0	3.44	92	52	<0.5	<5	5.86	13	33	301	106	6.18	<1	0.02	<10	3.29	2271	<2	<0.01	36	1378	83	3.33	<5	26	253	<5	<0.01	<10	<10	264	27	1144	6
8V2768RA/RJ	HL08-24	85229	108.30	109.70	1.40	0.74	2.6	0.61	431	73	<0.5	<5	2.76	13	10	60	58	6.35	<1	0.14	<10	0.81	1639	6	0.01	1	566	548	>5.00	<5	4	174	<5	<0.01	<10	<10	27	15	568	6
8V2768RA/RJ	HL08-24	85230	109.70	110.50	0.80	0.01	2.0	1.01	7	81	<0.5	<5	2.47	<1	11	53	<1	2.00	<1	0.25	<10	0.72	621	2	0.03	4														

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																												
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm	
8V2821RA/RJ	HL08-25	85272	77.20	78.70	1.50	0.02	0.4	0.55	31	401	<0.5	<5	2.48	<1	9	41	15	3.38	<1	0.37	<10	0.66	1813	2	0.01	1	799	18	0.93	<5	3	157	<5	<0.01	<10	<10	15	<10	82	2	
8V2821RA/RJ	HL08-25	85273	78.70	80.30	1.60	0.05	1.7	0.38	52	218	<0.5	<5	3.48	27	7	72	110	3.28	<1	0.33	<10	0.81	2072	2	0.01	1	678	988	1.39	<5	2	207	<5	<0.01	<10	<10	7	26	3135	2	
8V2821RA/RJ	HL08-25	85274	80.30	81.83	1.53	0.03	0.7	0.43	52	213	<0.5	<5	3.12	1	8	55	13	3.00	<1	0.34	<10	0.74	1967	<2	0.01	2	776	21	1.00	<5	2	177	<5	<0.01	<10	<10	7	<10	72	1	
8V2821RA/RJ	HL08-25	85275	Std	PM1110		1.76	173.0	0.96	193	216	<0.5	<5	79	4.83	5	17	21	3519	3.36	4	0.20	<10	0.17	640	65	0.03	33	657	234	1.39	209	2	185	<5	0.06	<10	<10	22	20	264	9
8V2821RA/RJ	HL08-25	85276	81.83	83.00	1.17	0.02	0.5	0.62	51	134	<0.5	<5	2.57	1	10	70	15	3.56	<1	0.40	<10	0.72	2048	2	0.01	1	893	49	1.65	<5	3	125	<5	<0.01	<10	<10	12	<10	136	2	
8V2821RA/RJ	HL08-25	85277	83.00	84.30	1.30	0.06	0.9	0.54	85	118	<0.5	<5	4.00	2	9	56	39	3.60	<1	0.29	<10	0.70	2147	<2	0.01	1	818	65	1.95	<5	3	165	<5	<0.01	<10	<10	14	<10	140	2	
8V2821RA/RJ	HL08-25	85278	84.30	85.60	1.30	0.04	0.6	1.63	37	117	<0.5	<5	2.82	2	10	58	24	3.85	<1	0.33	<10	0.81	1833	3	0.01	1	860	235	1.10	<5	4	105	<5	<0.01	<10	<10	38	<10	285	2	
8V2821RA/RJ	HL08-25	85279	85.60	86.90	1.30	0.06	0.6	1.31	24	95	<0.5	<5	4.43	<1	10	58	43	3.62	<1	0.26	<10	0.64	1971	<2	0.01	2	870	13	1.04	<5	3	132	<5	<0.01	<10	<10	36	<10	77	2	
8V2821RA/RJ	HL08-25	85280	86.90	88.75	1.85	0.04	0.9	0.49	48	81	<0.5	<5	8.79	1	7	40	20	2.89	<1	0.28	<10	0.57	2112	2	0.01	1	706	10	1.21	<5	3	310	<5	<0.01	<10	<10	14	<10	60	1	
8V2821RA/RJ	HL08-25	85281	88.75	90.58	1.83	0.05	0.8	0.55	96	191	<0.5	<5	3.63	2	9	77	18	3.33	<1	0.28	<10	0.60	2240	2	0.01	2	767	67	1.74	<5	2	161	<5	<0.01	<10	<10	17	<10	86	2	
8V2821RA/RJ	HL08-25	85282	90.58	92.20	1.62	0.01	0.6	1.36	33	312	<0.5	<5	4.12	2	10	38	28	3.78	<1	0.36	<10	0.73	2186	2	0.01	1	978	55	0.81	<5	3	163	<5	<0.01	<10	<10	30	<10	268	2	
8V2821RA/RJ	HL08-25	85283	92.20	93.80	1.60	<0.01	<0.1	1.93	20	134	<0.5	<5	3.53	<1	11	49	20	3.79	<1	0.38	11	0.70	1777	<2	0.01	1	993	15	0.61	<5	4	109	<5	<0.01	<10	<10	45	<10	99	2	
8V2821RA/RJ	HL08-25	85284	93.80	95.45	1.65	0.02	0.7	0.71	61	118	<0.5	<5	4.64	2	10	39	21	3.37	<1	0.39	<10	0.65	2467	2	0.01	1	914	35	1.09	<5	3	288	<5	<0.01	<10	<10	11	<10	164	2	
8V2821RA/RJ	HL08-25	85285	95.45	97.10	1.65	0.07	1.5	0.81	85	112	<0.5	<5	3.06	28	9	41	47	3.81	<1	0.35	<10	0.62	1888	2	0.01	1	860	303	1.93	<5	3	267	<5	<0.01	<10	<10	13	22	2815	2	
8V2821RA/RJ	HL08-25	85286	97.10	99.00	1.90	0.02	0.1	1.88	29	108	<0.5	<5	2.42	2	10	47	21	3.83	<1	0.34	<10	0.84	1858	3	0.01	1	940	21	0.82	<5	5	105	<5	0.01	<10	<10	44	<10	246	2	
8V2821RA/RJ	HL08-25	85287	99.00	100.80	1.80	0.04	0.7	1.68	87	108	<0.5	<5	2.64	2	9	53	33	3.86	<1	0.27	<10	0.81	2505	3	0.01	1	907	121	1.70	<5	3	102	<5	<0.01	<10	<10	39	<10	199	2	
8V2821RA/RJ	HL08-25	85288	100.80	102.50	1.70	0.06	0.9	1.26	133	112	<0.5	<5	2.84	5	10	56	36	3.96	<1	0.33	<10	0.69	2453	2	0.01	1	825	185	2.65	<5	3	106	<5	<0.01	<10	<10	26	<10	429	2	
8V2821RA/RJ	HL08-25	85289	102.50	104.20	1.70	0.08	1.9	1.03	164	112	<0.5	<5	2.62	5	10	68	61	3.67	<1	0.31	<10	0.64	2622	2	0.01	2	828	537	2.01	<5	3	113	<5	<0.01	<10	<10	21	<10	325	2	
8V2821RA/RJ	HL08-25	85290	104.20	105.90	1.70	0.04	1.1	1.58	88	130	<0.5	<5	2.17	2	9	68	59	3.59	<1	0.29	<10	0.72	2832	2	0.01	1	801	66	1.73	<5	3	85	<5	<0.01	<10	<10	39	<10	191	2	
8V2821RA/RJ	HL08-25	85291	105.90	107.50	1.60	0.09	1.5	0.49	121	83	<0.5	<5	2.55	4	6	115	15	2.58	<1	0.19	<10	0.17	1601	2	0.01	3	468	329	2.56	<5	1	81	<5	<0.01	<10	<10	12	<10	402	1	
8V2821RA/RJ	HL08-25	85292	107.50	109.10	1.60	0.09	1.1	0.44	165	93	<0.5	<5	3.50	5	6	98	17	2.67	<1	0.20	<10	0.13	1563	2	0.01	1	453	303	2.93	<5	1	86	<5	<0.01	<10	<10	13	<10	356	1	
8V2821RA/RJ	HL08-25	85293	109.10	110.70	1.60	0.12	1.0	0.37	238	120	<0.5	<5	2.13	6	8	113	20	3.25	<1	0.20	<10	0.10	899	2	0.01	3	694	131	3.77	<5	1	57	<5	<0.01	<10	<10	16	<10	289	2	
8V2821RA/RJ	HL08-25	85294	110.70	112.30	1.60	0.08	1.4	0.30	148	95	<0.5	<5	2.97	6	5	88	18	3.26	<1	0.19	<10	0.06	1469	3	0.01	1	502	325	2.64	<5	1	113	<5	<0.01	<10	<10	7	<10	465	1	
8V2821RA/RJ	HL08-25	85295	112.30	114.40	2.10	0.04	1.4	1.23	94	115	<0.5	<5	2.94	3	10	98	48	3.10	<1	0.23	<10	0.61	3943	2	0.01	3	901	75	1.67	<5	3	95	<5	<0.01	<10	<10	31	<10	307	2	
8V2821RA/RJ	HL08-25	85296	114.40	116.50	2.10	0.07	2.3	1.24	78	85	<0.5	<5	3.82	2	8	86	88	3.38	1	0.18	<10	0.64	4325	3	0.01	2	735	87	1.34	<5	3	83	<5	<0.01	<10	<10	36	<10	226	1	
8V2821RA/RJ	HL08-25	85297	116.50	118.60	2.10	0.10	2.8	1.22	122	89	<0.5	<5	4.89	4	8	81	91	3.28	<1	0.20	<10	0.61	4176	2	0.01	2	699	154	1.53	<5	3	116	<5	<0.01	<10	<10	32	<10	432	2	
8V2821RA/RJ	HL08-25	85298	118.60	120.30	1.70	0.28	5.4	0.52	249	71	<0.5	<5	7.20	19	5	66	138	3.14	<1	0.13	<10	0.32	2776	<2	0.01	2	457	1371	2.84	<5	2	182	<5	<0.01	<10	<10	17	15	1858	1	
8V2821RA/RJ	HL08-25	85299	120.30	122.20	1.90	0.04	0.8	1.27	63	106	<0.5	<5	2.63	3	10	83	48	3.92	<1	0.24	<10	0.80	1860	3	0.01	1	782	177	0.91	<5	4	107	<5	0.01	<10	<10	39	<10	311	2	
8V2821RA/RJ	HL08-25	85300	Blank	Blank	<0.01	<0.1	1.00	<5	272	0.7	<5	0.54	<1	9	112	<1	2.33	<1	0.52	<10	0.66	643	<2	0.06	6	776	10	0.01	<5	2	47	5	0.13	<10	<10	42	<10	64	2		
8V2821RA/RJ	HL08-25	85301	122.20	124.00	1.80	0.28	0.3	1.04	24	191	<0.5	<5	2.95	1	10	53	39	3.88	<1	0.28	<10	0.84	1666	4	0.02	1	889	14	0.79	<5	4	165	<5	<0.01	<10	<10	31	<10	12		

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:				S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Zr												
					0.5-1.0	1.0-3.0	3.0-5.0	>5.0	5-10	10-50	50-100	>100	2500-5000	5000-10000	>10000																									
8V2821RA/RJ	HL08-26	85343	62.90	63.75	0.85	0.01	0.7	2.52	48	117	<0.5	<5	6.02	1	25	14	33	5.95	<1	0.28	<10	1.48	2762	28	0.02	2	1155	77	1.10	<5	3	174	<5	0.05	<10	<10	71	<10	86	3
8V2821RA/RJ	HL08-26	85344	69.30	71.09	1.79	0.06	1.6	1.89	71	146	0.6	<5	5.14	2	21	5	108	5.29	<1	0.42	<10	0.98	2158	4	0.01	1	1418	31	2.13	<5	3	171	<5	0.08	<10	<10	56	<10	185	3
8V2821RA/RJ	HL08-26	85345	71.09	72.13	1.04	0.27	1.7	1.23	315	133	0.5	<5	7.07	5	21	22	24	5.76	<1	0.53	<10	0.51	2282	4	0.01	2	1442	64	>5.00	<5	3	213	<5	0.06	<10	<10	33	<10	97	3
8V2821RA/RJ	HL08-26	85346	72.13	73.40	1.27	0.03	2.5	2.21	62	154	0.6	<5	4.24	1	23	5	70	6.23	<1	0.46	<10	1.21	2354	<2	0.01	1	1482	35	2.65	<5	4	150	<5	0.08	<10	<10	73	<10	104	3
8V2821RA/RJ	HL08-26	85347	73.40	74.72	1.32	0.07	4.7	1.52	157	126	0.6	<5	5.12	2	25	9	115	6.19	<1	0.45	<10	0.68	1876	3	0.01	2	1594	73	4.81	<5	3	197	<5	0.07	<10	<10	48	<10	89	3
8V2821RA/RJ	HL08-26	85348	74.72	76.10	1.38	0.27	11.3	0.63	219	138	<0.5	<5	6.50	6	13	81	83	3.40	<1	0.43	<10	0.09	1770	3	0.01	2	777	189	3.98	<5	2	174	<5	0.01	<10	<10	16	<10	421	2
8V2821RA/RJ	HL08-26	85349	76.10	77.50	1.40	0.25	2.1	0.56	215	98	<0.5	<5	10.68	4	9	37	38	2.66	<1	0.21	<10	0.28	2686	7	0.01	1	618	29	2.23	<5	1	304	<5	<0.01	<10	<10	23	<10	116	1
8V2821RA/RJ	HL08-26	85350	Blank	Blank		<0.01	<0.1	1.21	<5	324	1.0	<5	0.73	<1	10	214	1	2.64	<1	0.56	12	0.66	736	2	0.09	9	802	16	0.02	<5	3	66	7	0.16	<10	<10	48	<10	67	3
8V2821RA/RJ	HL08-26	85351	77.50	79.00	1.50	0.34	5.0	1.08	914	144	<0.5	<5	3.44	17	16	41	168	4.29	<1	0.32	<10	0.50	1623	10	0.01	2	1033	73	3.03	9	2	129	<5	<0.01	<10	<10	39	<10	248	2
8V2821RA/RJ	HL08-26	85352	79.00	80.00	1.00	2.02	9.5	0.60	371	102	<0.5	<5	5.18	27	16	101	299	5.31	<1	0.35	<10	0.13	1602	4	0.01	3	924	1766	>5.00	<5	2	135	<5	0.01	<10	<10	23	20	2481	2
8V2821RA/RJ	HL08-26	85353	80.00	82.15	2.15	0.32	4.6	0.59	250	119	<0.5	<5	8.45	5	12	35	142	3.20	<1	0.28	<10	0.22	2543	11	0.01	1	835	78	3.20	<5	2	244	<5	0.01	<10	<10	19	<10	230	1
HL08-27 - Zone: Oxidantal, Pad 23: 435285E,6222782N, Elev:1173m, Az: 100, Dip: -45, EOH: 137.20m																																								
8V2821RA/RJ	HL08-27	85354	1.30	3.00	1.70	0.01	<0.1	0.95	<5	160	0.5	<5	0.98	<1	6	112	3	1.80	<1	0.34	29	0.32	290	<2	0.05	8	653	23	0.03	<5	2	36	9	<0.01	<10	<10	17	<10	55	6
8V2821RA/RJ	HL08-27	85355	3.00	5.00	2.00	0.30	<0.1	0.83	<5	135	<0.5	<5	1.02	<1	6	60	2	1.67	<1	0.29	29	0.31	286	<2	0.04	5	637	28	0.02	<5	2	39	10	<0.01	<10	<10	17	<10	64	8
8V2821RA/RJ	HL08-27	85356	5.00	7.00	2.00	<0.01	<0.1	0.80	<5	175	0.5	<5	1.41	<1	6	95	2	1.64	<1	0.32	29	0.28	278	<2	0.05	5	633	12	0.02	<5	2	58	9	<0.01	<10	<10	14	<10	37	6
8V2821RA/RJ	HL08-27	85357	7.00	9.00	2.00	<0.01	<0.1	0.71	<5	151	<0.5	<5	1.93	<1	5	59	2	1.53	<1	0.28	27	0.30	312	<2	0.04	4	581	12	0.08	<5	2	110	10	<0.01	<10	<10	11	<10	32	6
8V2821RA/RJ	HL08-27	85358	9.00	13.00	4.00	0.01	0.4	1.10	17	377	0.6	<5	1.27	<1	9	69	33	3.13	<1	0.50	19	0.23	945	2	0.03	3	978	16	0.39	<5	3	62	6	<0.01	<10	<10	20	<10	58	4
8V2821RA/RJ	HL08-27	85359	13.00	15.00	2.00	0.01	0.3	0.64	<5	184	<0.5	<5	2.67	<1	9	36	21	2.13	<1	0.35	17	0.51	803	2	0.03	4	886	16	0.25	<5	2	170	<5	<0.01	<10	<10	12	<10	60	4
8V2821RA/RJ	HL08-27	85360	15.00	16.45	1.45	0.01	0.1	0.57	8	441	0.5	<5	2.60	<1	10	37	33	2.14	<1	0.36	14	0.25	1210	4	0.03	3	909	17	0.43	<5	2	159	<5	<0.01	<10	<10	10	<10	70	4
8V2821RA/RJ	HL08-27	85361	16.45	18.46	2.01	0.50	6.0	0.43	350	90	<0.5	<5	2.41	7	11	72	90	4.14	<1	0.28	<10	0.21	852	3	0.01	2	873	47	4.36	<5	1	102	<5	<0.01	<10	<10	9	<10	225	2
8V2821RA/RJ	HL08-27	85362	18.46	20.00	1.54	0.01	1.1	0.72	200	215	<0.5	<5	3.10	<1	7	101	7	2.51	<1	0.43	11	0.15	1672	2	0.02	4	676	16	0.12	<5	2	56	<5	<0.01	<10	<10	9	<10	45	3
8V2821RA/RJ	HL08-27	85363	20.00	21.60	1.60	0.01	0.8	0.53	22	215	<0.5	<5	2.66	<1	8	56	6	2.56	<1	0.33	10	0.25	1668	<2	0.02	4	791	15	0.17	<5	2	60	<5	<0.01	<10	<10	7	<10	54	3
8V2821RA/RJ	HL08-27	85364	21.60	23.00	1.40	0.01	<0.1	0.46	15	67	0.5	<5	6.09	<1	10	22	13	3.74	<1	0.31	<10	1.41	2716	<2	0.01	3	975	14	0.30	<5	2	282	<5	<0.01	<10	<10	10	<10	82	2
8V2820RA/RJ	HL08-27	85365	23.00	24.35	1.35	0.02	2.7	0.39	16	54	0.5	<5	5.35	<1	11	19	16	4.15	<1	0.28	<10	1.47	2801	<2	0.01	1	1119	22	0.54	<5	2	266	<5	<0.01	<10	<10	11	<10	98	2
8V2820RA/RJ	HL08-27	85366	24.35	26.00	1.65	0.05	3.6	0.48	44	75	0.6	5	1.55	32	13	29	87	4.55	<1	0.35	<10	0.65	1596	2	0.01	2	1099	856	1.58	<5	2	69	<5	<0.01	<10	<10	22	29	3558	2
8V2820RA/RJ	HL08-27	85367	26.00	27.00	1.00	0.06	2.0	0.45	46	61	0.6	<5	1.90	7	12	45	32	4.48	<1	0.30	10	0.67	1902	<2	0.01	2	1065	1332	1.22	<5	2	81	<5	<0.01	<10	<10	15	<10	917	2
8V2820RA/RJ	HL08-27	85368	27.00	28.00	1.00	0.02	0.8	0.55	23	57	0.7	<5	1.93	1	15	29	29	4.16	<1	0.34	14	0.58	1560	3	0.01	2	1251	46	0.79	<5	3	94	<5	<0.01	<10	<10	15	<10	194	2
8V2820RA/RJ	HL08-27	85369	28.00	29.00	1.00	0.02	0.7	0.52	16	77	0.6	<5	1.51	1	14	35	34	4.29	<1	0.38	14	0.60	1869	<2	0.01	2	1154	46	0.70	<5	4	69	<5	<0.01	<10	<10	16	<10	248	2
8V2820RA/RJ	HL08-27	85370	29.00	30.30	1.30	0.03	0.8	0.53	15	63	0.6	<5	1.63	7	12	35	29	3.92	<1	0.38	14	0.64	1794	<2	0.01	2	1188	126	0.76	<5	3	66	<5	<0.01	<10	<10	16	<10	876	1
8V2820RA/RJ	HL08-27	85371	30.30	31.60	1.30	0.13	1.8	0.45	42	64	0.5	<5	2.17	1	14	40	31	3.96	<1	0.35	10	0.56	1758	<2	0.01	2	1148	44	0.95	<5	3	90	<5	<0.01	<10	<10	16	<10	132	2
8V2820RA/RJ	HL08-27	85372	37.00	37.47	0.47	0.04	1.7	1.49	13	189	0.5	<5	2.45	<1	11	63	184	2.92	<1	0.39	13	0.61	917	11	0.04	3	807	20	0.57	<5	2	122	<5	<0.01	<10	<10	29	<10	77	4
8V2820RA/RJ	HL08-27	85373	37.47	38.80	1.33																																			

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																										
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V2819A/RJ	HL08-29	85412	10.00	12.00	2.00	0.27	41.9	1.18	288	111	<0.5	<5	0.85	8	13	191	22	4.25	<1	0.47	<10	0.28	576	2	0.02	7	982	202	3.39	5	2	38	<5	<0.01	<10	<10	21	<10	453	3
8V2819A/RJ	HL08-29	85413	12.00	14.00	2.00	0.35	6.3	0.85	254	123	<0.5	<5	0.72	5	13	72	14	4.49	<1	0.27	<10	0.28	584	<2	0.01	4	836	42	3.88	<5	2	44	<5	<0.01	<10	<10	13	<10	125	2
8V2819A/RJ	HL08-29	85414	14.00	15.00	1.00	0.47	6.6	1.27	318	120	<0.5	<5	0.66	7	13	142	28	4.49	<1	0.44	<10	0.37	621	2	0.02	6	1131	50	3.39	<5	2	33	<5	<0.01	<10	<10	20	<10	265	3
8V2819A/RJ	HL08-29	85415	15.00	16.23	1.23	0.26	6.2	0.79	337	103	<0.5	<5	1.63	7	13	54	16	4.97	<1	0.28	<10	0.27	769	<2	0.01	5	577	44	4.82	<5	2	58	<5	<0.01	<10	<10	12	<10	95	2
8V2819A/RJ	HL08-29	85416	16.23	17.60	1.37	0.33	16.1	1.09	324	134	<0.5	<5	1.20	8	13	93	11	4.40	<1	0.39	<10	0.35	733	<2	0.02	3	892	95	3.65	<5	2	45	<5	<0.01	<10	<10	21	<10	342	3
8V2819A/RJ	HL08-29	85417	17.60	19.60	2.00	0.36	8.2	1.13	268	192	<0.5	<5	0.76	6	12	69	13	4.05	<1	0.32	<10	0.42	781	<2	0.01	2	916	55	2.67	<5	2	31	<5	0.03	<10	<10	24	<10	168	3
8V2819A/RJ	HL08-29	85418	19.60	21.60	2.00	0.30	20.0	1.12	287	149	<0.5	<5	0.76	6	13	98	15	4.32	<1	0.37	<10	0.40	974	2	0.01	3	890	81	3.29	<5	2	31	<5	0.04	<10	<10	24	<10	152	3
8V2819A/RJ	HL08-29	85419	21.60	23.60	2.00	0.38	8.5	0.97	204	200	<0.5	<5	1.26	4	11	67	18	3.51	<1	0.30	<10	0.34	1293	<2	0.01	2	1006	28	2.35	<5	2	45	<5	0.03	<10	<10	19	<10	77	2
8V2819A/RJ	HL08-29	85420	23.60	25.50	1.90	0.54	35.9	0.62	340	81	<0.5	<5	1.52	7	13	137	19	4.88	<1	0.40	<10	0.08	1178	2	0.01	4	918	91	>5.00	6	2	48	<5	0.03	<10	<10	14	<10	89	2
8V2819A/RJ	HL08-29	85421	25.50	27.50	2.00	0.02	1.2	2.03	20	228	0.7	<5	2.41	<1	19	27	12	4.98	<1	0.33	<10	0.99	1974	<2	0.02	1	1395	19	1.54	<5	3	67	<5	0.08	<10	<10	39	<10	122	3
8V2819A/RJ	HL08-29	85422	33.70	34.70	1.00	0.03	3.4	1.26	107	149	<0.5	<5	3.45	2	19	67	14	4.92	<1	0.33	<10	0.52	1708	<2	0.02	2	1443	23	3.56	<5	3	95	<5	0.04	<10	<10	28	<10	73	2
8V2819A/RJ	HL08-29	85423	39.00	40.35	1.35	0.24	171.6	0.95	74	205	<0.5	<5	1.38	1	13	78	35	3.80	<1	0.31	<10	0.28	827	14	0.03	3	988	24	2.52	6	2	49	<5	0.03	<10	<10	30	<10	67	3
8V2819A/RJ	HL08-29	85424	40.35	41.70	1.35	0.66	8.8	0.87	74	177	<0.5	<5	3.79	1	12	119	16	3.68	<1	0.38	<10	0.20	994	63	0.03	3	824	27	3.06	<5	3	124	<5	0.03	<10	<10	24	<10	56	3
8V3672A/RJ	HL08-29	122692	41.70	43.00	1.30	0.55	2.5	1.52	68	232	<0.5	<5	2.14	2	18	14	31	4.80	<1	0.38	<10	0.57	1340	3	0.03	3	1241	20	2.26	<5	3	83	<5	0.06	<10	<10	41	<10	47	4
8V3672A/RJ	HL08-29	122693	43.00	45.00	2.00	0.36	16.3	1.79	67	229	<0.5	<5	3.32	3	25	19	49	5.69	<1	0.34	<10	0.69	2139	<2	0.02	5	1024	33	2.31	<5	4	101	<5	0.06	<10	<10	38	<10	184	3
8V3672A/RJ	HL08-29	122694	45.00	47.00	2.00	0.16	7.5	2.18	64	260	<0.5	<6	1.51	3	25	15	40	6.14	<1	0.40	<10	0.80	1934	<2	0.03	6	1305	32	1.89	<5	4	45	<5	0.03	<10	<10	46	<10	153	3
8V3672A/RJ	HL08-29	122695	47.00	49.00	2.00	0.08	6.2	1.22	110	256	<0.5	<6	1.35	4	17	48	34	5.05	<1	0.34	<10	0.41	1175	<2	0.02	6	1073	33	2.77	<5	2	50	<5	0.01	<10	<10	23	<10	102	3
8V3672A/RJ	HL08-29	122696	49.00	51.00	2.00	0.03	3.7	2.11	66	207	<0.5	<7	1.58	2	20	13	32	5.48	<1	0.29	<10	0.91	2008	2	0.03	5	1330	28	1.24	<5	4	51	<5	0.01	<10	<10	40	<10	104	3
8V3672A/RJ	HL08-29	122697	51.00	53.00	2.00	0.03	3.8	2.19	37	217	<0.5	<6	1.85	2	19	34	44	5.48	<1	0.32	<10	0.96	2189	<2	0.03	6	1285	25	1.14	<5	3	56	<5	0.01	<10	<10	41	<10	113	3
8V3672A/RJ	HL08-29	122698	53.00	55.00	2.00	0.08	5.2	1.92	86	192	<0.5	<6	0.92	3	21	11	45	5.67	1	0.35	<10	0.75	1528	<2	0.02	6	951	33	2.27	<5	3	36	<5	0.01	<10	<10	32	<10	102	3
8V3672A/RJ	HL08-29	122699	55.00	57.00	2.00	0.03	5.6	1.19	34	221	<0.5	<6	0.60	2	21	21	62	4.58	1	0.32	<10	0.92	1723	<2	0.02	6	1105	29	1.25	<5	3	22	<5	0.01	<10	<10	39	<10	132	3
8V3672A/RJ	HL08-29	122700	57.00	59.00	2.00	0.03	2.2	2.20	61	243	<0.5	<6	2.24	2	19	10	39	5.29	<1	0.37	<10	0.89	2128	<2	0.03	5	1389	21	1.39	<5	4	71	<5	0.01	<10	<10	40	<10	93	3
8V3672A/RJ	HL08-29	122701	59.00	61.00	2.00	<0.01	1.2	2.74	17	221	<0.5	<5	1.82	1	20	10	34	5.83	<1	0.30	<10	1.16	2326	<2	0.02	5	1336	20	0.30	<5	4	56	<5	0.03	<10	<10	45	<10	104	3
8V3672A/RJ	HL08-29	122702	61.00	63.00	2.00	0.02	2.0	1.90	94	178	<0.5	<5	1.33	3	22	12	24	5.52	<1	0.35	<10	0.83	1600	<2	0.03	5	1571	22	2.42	<5	3	51	<5	0.06	<10	<10	39	<10	95	3
8V3672A/RJ	HL08-29	122703	63.00	65.00	2.00	0.02	3.5	2.15	37	211	<0.5	<5	1.61	2	21	24	37	5.50	<1	0.30	<10	1.03	2184	<2	0.03	5	1399	25	1.55	<5	4	52	<5	0.05	<10	<10	45	<10	127	3
8V3672A/RJ	HL08-29	122704	65.00	67.00	2.00	<0.01	1.6	2.40	5	224	<0.5	<5	2.93	1	20	7	38	5.27	<1	0.32	<10	1.10	2377	<2	0.03	5	1563	19	0.49	<5	4	84	<5	0.07	<10	<10	50	<10	95	3
8V3672A/RJ	HL08-29	122705	67.00	69.00	2.00	0.01	1.9	2.33	18	236	<0.5	<5	2.61	1	27	11	39	5.20	<1	0.33	<10	1.02	2535	<2	0.03	5	1237	19	0.43	<5	4	78	<5	0.04	<10	<10	39	<10	95	2
8V3672A/RJ	HL08-29	122706	69.00	71.00	2.00	<0.01	1.7	2.08	75	306	<0.5	<5	1.66	3	19	8	39	4.36	<1	0.39	<10	0.89	2199	<2	0.03	4	1013	21	0.53	<5	3	66	<5	0.01	<10	<10	29	<10	82	2
8V3672A/RJ	HL08-29	122707	71.00	73.00	2.00	0.03	2.9	1.98	132	285	<0.5	<6	2.11	4	17	12	46	4.52	<1	0.36	<10	0.92	2114	<2	0.03	4	1178	20	0.94	<5	3	91	<5	<0.01	<10	<10	30	<10	100	2
8V3672A/RJ	HL08-29	122708	73.00	73.90	0.90	0.02	2.5	2.00	187	240	<0.5	<5	2.64	6	19	8	80	4.99	<1	0.33	<10	0.94	2273	<2	0.03	4	1269	18	1.28	<5	4	116	<5	0.01	<10	<10	35	<10	94	

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																												
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm	
8V2819RA/RJ	HL08-31	85465	34.15	36.00	1.85	0.02	2.9	1.76	144	94	<0.5	<5	1.40	2	21	41	23	7.52	<1	0.25	10	0.73	1705	<2	0.01	<1	1192	23	4.95	<5	2	39	<5	0.02	<10	<10	48	<10	110	3	
8V2819RA/RJ	HL08-31	85466	36.00	37.40	1.40	0.25	4.0	1.66	84	102	<0.5	<5	1.85	2	19	35	19	6.45	<1	0.27	14	0.66	1755	<2	0.01	<1	1664	33	3.72	<5	3	61	<5	0.01	<10	<10	53	<10	127	3	
8V2819RA/RJ	HL08-31	85467	37.40	38.75	1.35	0.02	1.7	2.54	65	165	<0.5	<5	0.94	1	20	25	32	7.51	<1	0.23	12	1.07	2294	<2	0.01	<1	1581	66	2.31	<5	3	33	<5	0.01	<10	<10	78	<10	215	3	
8V2819RA/RJ	HL08-31	85468	38.75	40.18	1.43	0.10	0.9	1.87	40	245	<0.5	<5	0.40	1	14	23	11	5.24	<1	0.24	14	0.83	1629	<2	0.01	<1	1002	46	1.26	<5	3	20	<5	<0.01	<10	<10	53	<10	188	2	
8V2819RA/RJ	HL08-31	85469	40.18	41.00	0.82	0.10	1.1	0.96	64	196	<0.5	<5	1.08	1	14	54	9	3.90	<1	0.30	12	0.36	1063	<2	0.01	<2	1075	26	2.43	<5	2	77	<5	<0.01	<10	<10	54	<10	64	2	
8V2819RA/RJ	HL08-31	85470	41.00	41.40	0.40	0.18	5.0	0.64	150	155	<0.5	<5	0.81	3	12	58	7	3.99	<1	0.28	11	0.20	681	4	0.01	<2	777	38	3.44	<5	1	46	<5	<0.01	<10	<10	14	<10	60	2	
8V2819RA/RJ	HL08-31	85471	41.00	42.17	0.77	0.02	1.8	1.10	62	276	<0.5	<5	0.28	1	14	40	26	4.57	<1	0.24	17	0.26	827	<2	0.02	3	1123	20	0.93	<5	3	12	<5	<0.01	<10	<10	24	<10	100	2	
8V2819RA/RJ	HL08-31	85472	42.17	43.68	1.51	0.01	3.5	1.33	38	116	<0.5	<5	0.45	1	11	31	19	3.77	1	0.17	14	0.59	1067	<2	0.02	4	977	10	0.97	5	2	18	<5	<0.01	<10	<10	33	<10	78	3	
8V2819RA/RJ	HL08-31	85473	43.68	45.09	1.41	<0.01	1.4	1.67	38	156	<0.5	<5	0.32	1	14	25	22	4.12	1	0.19	15	0.81	1331	<2	0.01	5	829	5	0.73	<5	2	23	<5	<0.01	<10	<10	34	<10	90	3	
8V2819RA/RJ	HL08-31	85474	45.09	46.80	1.71	0.08	1.8	1.18	57	136	<0.5	<5	0.42	1	11	36	17	3.82	1	0.21	14	0.52	941	<2	0.02	4	862	9	1.79	<5	2	19	<5	<0.01	<10	<10	30	<10	74	3	
8V2819RA/RJ	HL08-31	85475	Std	PM922			5.94	2.7	1.96	585	271	0.8	180	9.52	2	48	141	468	6.87	12	0.22	18	0.41	1140	109	0.06	72	831	77	2.13	5	4	117	8	0.17	<10	<10	59	22	89	25
8V2819RA/RJ	HL08-31	85476	46.80	47.50	0.70	0.12	5.3	0.95	96	142	<0.5	<5	0.18	1	10	67	24	3.25	1	0.16	13	0.45	817	3	0.01	4	580	27	0.84	5	1	10	<5	<0.01	<10	<10	19	<10	104	2	
8V2819RA/RJ	HL08-31	85477	47.50	49.50	2.00	0.13	3.8	1.51	42	151	<0.5	<5	0.59	1	12	36	20	3.55	1	0.20	11	0.86	1220	<2	0.02	4	920	21	0.84	<5	2	26	<5	0.01	<10	<10	30	<10	108	3	
8V2819RA/RJ	HL08-31	85478	49.50	51.50	2.00	0.02	1.9	1.71	37	183	<0.5	<5	2.01	1	13	30	19	3.75	<1	0.20	12	1.04	1870	<2	0.02	3	893	21	0.74	<5	2	83	<5	0.02	<10	<10	35	<10	80	3	
8V2819RA/RJ	HL08-31	85479	51.50	53.50	2.00	0.02	2.0	1.92	18	125	<0.5	<5	1.64	1	14	24	17	3.99	1	0.18	<10	1.16	1942	<2	0.02	3	969	9	0.47	<5	3	57	<5	0.04	<10	<10	41	<10	105	3	
8V2819RA/RJ	HL08-31	85480	53.50	55.63	2.13	0.04	25.1	1.55	30	119	<0.5	<5	3.09	2	16	24	20	3.87	<1	0.18	<10	0.91	2178	<2	0.01	4	914	43	1.17	6	2	110	<5	0.05	<10	<10	37	<10	290	3	
8V2819RA/RJ	HL08-31	85481	55.63	57.61	1.98	0.05	10.0	1.42	88	112	<0.5	<5	1.20	1	19	21	37	4.94	1	0.20	10	0.74	1608	<2	0.01	6	1210	31	2.62	5	2	54	<5	0.04	<10	<10	33	<10	93	4	
8V2819RA/RJ	HL08-31	85482	57.61	59.63	2.02	0.02	20.6	1.74	29	134	<0.5	<5	0.63	2	19	23	42	4.78	1	0.21	10	0.81	1741	<2	0.02	6	1120	84	1.35	<5	2	30	<5	0.02	<10	<10	39	<10	172	3	
8V2819RA/RJ	HL08-31	85483	59.63	61.28	1.65	0.02	8.8	1.73	77	143	<0.5	<5	0.66	1	17	21	35	4.18	1	0.21	<10	0.81	1914	<2	0.02	6	1141	11	0.68	<5	2	36	<5	0.02	<10	<10	37	<10	90	3	
HL08-32 - Zone: Snow Show, Pad 25: 435176E,6223339N, Elev:1219m, Az:040, Dip: -65, EOH: 200.30m																																									
8V2892RA/RJ	HL08-32	85484	4.41	6.41	2.00	0.16	2.00	2.03	23.00	110.00	1.20	<5	2.94	2.00	21.00	43.00	130	5.27	<1	0.09	10	1.32	1219	3	0.03	<1	1303	6	0.22	<5	7	101	5	0.22	<10	<10	128	<10	254	5	
8V2892RA/RJ	HL08-32	85485	6.41	8.41	2.00	0.25	1.7	1.90	112	81	0.5	<5	3.07	2	18	61	75	5.64	1	0.14	<10	1.04	1463	2	0.03	3	1210	15	0.66	<5	7	107	5	0.07	<10	<10	125	<10	187	4	
8V2892RA/RJ	HL08-32	85486	8.41	10.41	2.00	0.28	1.1	1.88	87	77	0.8	<5	3.64	3	20	38	38	5.12	1	0.16	10	1.08	1897	6	0.03	1	1162	42	0.43	<5	7	108	5	0.12	<10	<10	113	<10	306	4	
8V2892RA/RJ	HL08-32	85487	10.41	11.76	1.35	0.27	0.6	2.02	28	90	0.8	<5	3.19	4	19	44	48	5.25	1	0.22	10	1.14	1679	6	0.03	1	1222	83	0.29	<5	7	115	<5	0.10	<10	<10	111	<10	414	5	
8V2892RA/RJ	HL08-32	85488	11.76	12.40	0.64	0.19	0.9	2.06	27	89	0.7	<5	3.25	4	19	44	48	5.35	2	0.22	10	1.14	1709	6	0.02	1	1246	82	0.30	<5	7	117	5	0.10	<10	<10	110	<10	414	4	
8V2892RA/RJ	HL08-32	85489	12.40	13.16	0.76	1.42	1.5	1.75	160	81	<0.5	<5	1.62	8	15	61	24	5.08	2	0.20	<10	1.01	1850	5	0.01	2	996	346	1.26	<5	4	50	<5	0.04	<10	<10	73	<10	1219	4	
8V2892RA/RJ	HL08-32	85490	13.16	14.64	1.48	0.86	3.5	1.05	290	92	<0.5	<5	1.68	20	11	93	87	5.09	<1	0.14	<10	0.83	1705	4	0.01	2	765	488	2.69	<5	3	56	<5	<0.01	<10	<10	57	19	2000	2	
8V2892RA/RJ	HL08-32	85491	14.64	15.70	1.06	0.32	1.9	1.33	257	84	<0.5	<5	2.59	5	18	60	114	4.70	<1	0.18	<10	0.79	1798	6	0.01	2	980	112	1.42	<5	5	76	<5	<0.01	<10	<10	76	<10	269	2	
8V2892RA/RJ	HL08-32	85492	15.70	17.50	1.80	0.17	1.6	0.81	57	153	<0.5	<5	4.27	1	15	56	131	4.54	<1	0.28	<10	0.75	1830	6	0.01	1	963	19	0.87	<5	6	299	<5	<0.01	<10	<10	33	<10	101	2	
8V2936RA/RJ	HL08-32	85493	17.50	19.12	1.62	0.08	1.4	1.77	74	109	<0.5	<5	4.69	22	30	168	70	5.59	<1	0.28	<10	0.87	1779	8	0.03	4	1204	14	0.87	<5	8	175	<5	0.02	<10	<10	106	<10	138	3	
8V2936RA/RJ	HL08-32	85494	19.12	21.09	1.97	0.19	1.1	1.67	152	85	<0.5	<5	4.72	20	36	121	69	5.28	<1	0.23	<10	0.86	2072	4	0.02	2	1073	21	1.59	<5	6	117	<5	0.02	<10	<10	98	<10	133	3</	

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																											
					Au g/t	Ag g/t	Al %	As ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm		
8V2936RA/RJ	HIL08-32	120036	87.73	89.48	1.75	0.06	0.4	1.64	51	88	<0.5	<5	2.28	1	16	55	57	4.58	<1	0.32	<10	1.05	1124	5	0.02	4	1046	7	1.25	<5	4	69	<5	<0.01	<10	<10	63	<10	90	2
8V2936RA/RJ	HIL08-32	120037	89.48	91.10	1.62	0.13	0.6	1.23	141	103	<0.5	<5	4.11	2	14	84	49	4.79	<1	0.23	<10	1.05	1690	5	0.01	3	1150	12	2.36	<5	3	87	<5	<0.01	<10	<10	52	<10	60	2
8V2936RA/RJ	HIL08-32	120038	91.10	92.92	1.82	0.06	8.0	1.70	312	132	<0.5	<5	0.63	5	14	64	24	7.23	1	0.23	<10	1.35	1290	<2	0.01	2	1798	101	2.80	10	4	6	<5	<0.01	<10	<10	65	<10	199	3
8V2936RA/RJ	HIL08-32	120039	92.92	93.60	0.68	0.17	0.5	0.76	61	230	0.6	<5	2.85	1	12	99	50	3.90	<1	0.27	<10	0.82	1346	7	0.01	4	1089	7	1.11	<5	3	77	<5	<0.01	<10	<10	28	<10	58	2
8V3008RA/RJ	HIL08-32	120046	93.60	94.17	0.57	0.04	0.2	0.64	27	101	<0.5	<5	2.34	<1	10	47	50	1.33	<1	0.32	<10	0.93	1171	10	0.02	1	913	9	0.50	<5	4	125	<5	<0.01	<10	<10	20	<10	46	2
8V3008RA/RJ	HIL08-32	120047	94.17	95.92	1.75	0.13	0.4	1.09	75	71	<0.5	<5	2.61	1	10	65	14	3.84	<1	0.32	<10	0.88	1165	4	0.01	2	894	11	0.96	<5	2	97	<5	<0.01	<10	<10	30	<10	67	2
8V3008RA/RJ	HIL08-32	120048	95.92	97.60	1.68	0.07	0.4	1.38	20	79	<0.5	<5	3.07	<1	11	43	31	3.88	<1	0.23	<10	0.87	1177	4	0.02	1	917	9	0.56	<5	3	84	<5	<0.01	<10	<10	47	<10	73	2
8V3008RA/RJ	HIL08-32	120049	97.60	99.18	1.58	0.04	0.7	1.23	29	75	<0.5	<5	3.10	<1	10	56	51	3.55	<1	0.20	<10	0.84	1218	5	0.02	2	882	10	0.52	<5	4	89	<5	<0.01	<10	<10	48	<10	81	2
8V3008RA/RJ	HIL08-32	120050	Blank	Blank	<0.01	<0.1	0.93	<5	229	<0.5	<5	0.44	<1	9	104	<1	2.03	<1	0.48	<10	0.60	555	<2	0.06	5	767	6	<0.01	<5	2	43	5	0.12	<10	<10	38	<10	50	2	
8V3008RA/RJ	HIL08-32	120051	99.18	101.06	1.88	0.08	0.7	0.77	81	100	<0.5	<5	3.57	1	10	53	26	3.23	<1	0.36	<10	0.78	1420	2	0.02	2	876	27	0.63	<5	4	152	<5	<0.01	<10	<10	21	<10	59	2
8V3008RA/RJ	HIL08-32	120052	101.06	102.40	1.34	0.03	0.5	0.69	48	196	<0.5	<5	3.01	1	11	68	8	3.44	<1	0.30	<10	0.79	1108	3	0.01	2	908	62	0.80	<5	3	136	<5	<0.01	<10	<10	23	<10	123	2
8V3008RA/RJ	HIL08-32	120053	102.40	103.75	1.35	0.10	0.4	0.65	30	264	<0.5	<5	3.51	2	11	34	59	3.91	1	0.37	<10	0.76	1298	3	0.02	5	993	6	0.49	<5	3	154	8	<0.01	<10	<10	30	<10	73	3
8V3008RA/RJ	HIL08-32	120054	103.75	105.35	1.60	0.12	3.4	0.50	67	243	<0.5	<5	2.48	18	14	46	223	4.49	<1	0.35	<10	0.83	1155	11	0.02	5	972	1553	0.95	<5	3	158	5	<0.01	<10	<10	25	<10	2160	3
8V3008RA/RJ	HIL08-32	120055	105.35	107.14	1.79	0.17	0.8	0.47	161	144	<0.5	<5	2.74	2	8	45	31	3.33	<1	0.33	<10	0.48	1051	3	0.01	3	777	259	1.62	<5	2	142	6	<0.01	<10	<10	17	<10	188	3
8V3008RA/RJ	HIL08-32	120056	107.14	108.64	1.50	0.08	0.3	0.84	45	153	<0.5	<5	2.94	2	11	50	27	3.62	<1	0.31	<10	0.63	1305	2	0.01	4	833	20	0.70	<5	2	106	5	<0.01	<10	<10	34	<10	80	3
8V3008RA/RJ	HIL08-32	120057	108.64	110.26	1.62	0.13	0.9	0.98	287	76	<0.5	<5	2.27	2	9	41	17	4.65	<1	0.31	<10	0.55	1253	4	0.01	4	739	15	2.39	5	2	93	5	<0.01	<10	<10	31	<10	48	4
8V3008RA/RJ	HIL08-32	120058	110.26	110.98	0.72	0.06	0.5	1.11	63	288	<0.5	<5	3.13	2	14	42	43	4.07	<1	0.29	<10	0.74	1195	9	0.01	6	879	10	0.92	<5	3	159	6	<0.01	<10	<10	39	<10	87	3
8V3008RA/RJ	HIL08-32	120059	110.98	112.82	1.84	0.03	0.4	0.88	48	192	<0.5	<5	2.80	8	10	30	34	3.44	<1	0.34	<10	0.66	1064	2	0.02	4	924	104	0.62	<5	3	119	7	<0.01	<10	<10	31	<10	914	3
8V3008RA/RJ	HIL08-32	120060	112.82	114.98	2.16	0.07	<0.1	1.23	196	190	<0.5	<5	3.02	2	10	44	24	3.61	<1	0.36	<10	0.74	1030	4	0.02	4	885	8	0.62	<5	3	148	7	<0.01	<10	<10	42	<10	68	3
8V3008RA/RJ	HIL08-32	120061	114.98	117.01	2.03	0.03	<0.1	1.12	34	145	<0.5	<5	3.04	1	10	26	15	3.70	<1	0.38	<10	0.84	1123	3	0.02	4	949	4	0.52	<5	4	166	7	<0.01	<10	<10	35	<10	52	3
8V3008RA/RJ	HIL08-32	120062	117.01	118.36	1.35	0.02	0.9	1.23	39	107	<0.5	<5	2.94	2	10	38	26	3.66	<1	0.34	<10	0.87	1071	12	0.02	3	913	25	0.49	<5	4	141	7	<0.01	<10	<10	38	<10	89	3
8V3008RA/RJ	HIL08-32	120063	118.36	119.97	1.61	0.04	0.2	0.77	46	115	<0.5	<5	2.17	1	9	35	13	3.36	<1	0.40	<10	0.71	1034	8	0.01	4	854	7	0.54	<5	3	106	7	<0.01	<10	<10	22	<10	46	3
8V3008RA/RJ	HIL08-32	120064	119.97	121.97	2.00	0.08	0.6	0.71	40	151	<0.5	<5	2.66	1	9	39	20	3.40	<1	0.31	<10	0.71	1091	11	0.02	3	883	4	0.51	<5	3	159	7	<0.01	<10	<10	25	<10	45	3
8V3008RA/RJ	HIL08-32	120065	121.97	123.72	1.75	0.10	0.2	0.51	30	102	<0.5	<5	3.07	1	7	42	15	3.15	1	0.33	<10	0.67	1028	8	0.02	2	760	15	0.43	<5	3	232	6	<0.01	<10	<10	17	<10	57	3
8V3008RA/RJ	HIL08-32	120066	123.72	125.67	1.95	0.27	0.6	0.63	422	80	<0.5	<5	4.37	1	8	45	11	3.25	<1	0.30	<10	0.50	1511	4	0.01	3	887	15	1.19	6	3	110	5	<0.01	<10	<10	21	<10	59	3
8V3008RA/RJ	HIL08-32	120067	125.67	127.61	1.94	0.21	1.2	0.58	170	66	<0.5	<5	2.03	2	10	36	87	3.87	<1	0.35	<10	0.54	1157	13	0.01	3	814	30	1.36	6	2	89	5	<0.01	<10	<10	21	<10	102	3
8V3008RA/RJ	HIL08-32	120068	127.61	129.39	1.78	0.32	2.4	0.65	126	70	0.5	<5	3.78	2	16	23	366	4.44	<1	0.42	<10	0.67	1694	9	0.01	4	1066	18	1.06	6	3	124	<5	<0.01	<10	<10	31	<10	145	3
8V3008RA/RJ	HIL08-32	120069	129.39	131.27	1.88	0.25	4.9	0.49	56	84	<0.5	<5	3.48	3	15	21	230	4.67	1	0.43	<10	0.80	1677	8	0.01	4	1109	38	0.90	36	5	273	5	<0.01	<10	<10	22	<10	147	3
8V3008RA/RJ	HIL08-32	120070	131.27	133.23	1.96	0.21	1.5	1.28	40	190	<0.5	<5	2.89	2	18	17	227	4.80	<1	0.46	<10	0.98	1645	6	0.01	5	1286	6	0.45	<5	5	135	6	<0.01	<10	<10	53	<10	199	3
8V3008RA/RJ	HIL08-32	120071	133.23	135.32	2.09	0.27	2.4	0.65	212	171	0.5	<5	4.04	2	15	14	214	4.60	<1	0.42	<10	0.79	1725	11	0.01	4	1115	51	1.64	7	3	154	5	<0.01	<10	<10	27	<10	198	3
8V3008RA/RJ	HIL08-32	120072	135.32	137.14	1.82	0.16	4.0																																	

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3008RA/RJ	HL08-33	120114	198.14	200.30	2.16	0.11	4.6	0.95	101	142	<0.5	<5	2.53	2	10	24	32	3.56	1	0.33	<10	0.57	1324	3	0.02	3	1010	56	1.40	<5	2	124	6	<0.01	<10	<10	24	<10	214	3
HL08-33 - Zone: Snow Show, Pad 25: 435177E,6223340N, Elev: 1219m, Az: 040, Dip: -45, EOH: 153.66m																																								
8V3008RA/RJ	HL08-33	120115	2.15	3.50	1.35	0.31	0.3	1.97	11	93	1.1	<5	1.24	3	17	23	51	4.68	<1	0.13	10	1.11	1127	<2	0.05	3	1343	14	0.15	<5	6	58	<5	0.21	<10	<10	102	<10	341	9
8V3008RA/RJ	HL08-33	120116	3.50	5.00	1.50	0.15	0.9	2.10	42	64	0.6	<5	2.31	3	17	28	80	5.25	1	0.10	<10	1.41	1450	2	0.03	2	1135	60	0.45	<5	7	122	6	0.10	<10	<10	117	<10	333	5
8V3008RA/RJ	HL08-33	120117	5.00	6.20	1.20	0.10	0.3	2.09	10	190	1.1	<5	2.10	2	18	57	4.86	<1	0.13	<10	1.46	973	3	0.03	3	1279	4	0.25	<5	7	131	<5	0.20	<10	<10	120	<10	168	5	
8V3063RA/RJ	HL08-33	120118	6.20	7.80	1.60	0.08	1.1	1.49	107	103	<0.5	<5	3.59	4	17	40	105	4.60	<1	0.17	<10	0.95	2180	4	0.01	1	955	59	0.49	<5	6	54	<5	0.09	<10	<10	91	<10	396	2
8V3063RA/RJ	HL08-33	120119	7.80	9.40	1.60	0.40	1.1	1.28	284	107	<0.5	<5	3.23	6	15	48	61	4.55	<1	0.15	<10	0.83	2138	3	0.01	2	861	64	1.24	<5	4	57	<5	0.05	<10	<10	77	<10	268	2
8V3063RA/RJ	HL08-33	120120	9.40	11.00	1.60	0.24	2.3	1.53	232	86	<0.5	<5	2.51	11	12	55	33	5.19	<1	0.12	<10	1.25	2372	5	0.01	1	833	627	1.32	<5	4	55	<5	<0.01	<10	<10	80	10	1108	2
8V3063RA/RJ	HL08-33	120121	11.00	11.55	0.55	0.64	11.7	0.67	725	26	<0.5	<6	0.99	45	8	69	61	11.72	<1	0.06	<10	0.50	1115	<2	<0.01	1	607	524	>5.00	13	1	39	<5	<0.01	<10	14	33	42	4681	5
8V3063RA/RJ	HL08-33	120122	11.55	13.65	2.10	0.14	2.1	1.13	320	103	<0.5	<5	2.88	7	10	92	40	3.70	<1	0.18	<10	0.73	1612	5	0.01	2	670	141	0.93	<5	3	64	<5	0.01	<10	<10	42	<10	229	2
8V3063RA/RJ	HL08-33	120123	13.65	15.75	2.10	0.13	0.5	1.09	81	79	<0.5	<5	3.41	2	9	79	28	3.67	<1	0.19	<10	0.71	1568	4	0.01	2	711	21	1.02	<5	3	75	<5	0.01	<10	<10	41	<10	75	2
8V3063RA/RJ	HL08-33	120124	15.75	17.85	2.10	0.31	0.7	1.15	86	145	<0.5	<5	2.89	2	11	116	61	3.99	<1	0.22	<10	0.75	1458	11	0.01	3	733	16	1.30	<5	3	70	<5	<0.01	<10	<10	42	<10	136	2
8V3063RA/RJ	HL08-33	120125	Std	PM1110		1.76	160.0	0.85	185	215	<0.5	<86	6.05	5	17	26	3907	3.95	3	0.16	<10	0.20	691	57	0.03	34	565	226	1.43	167	2	175	<5	0.07	<10	<10	24	<10	282	9
8V3063RA/RJ	HL08-33	120126	17.85	19.72	1.87	0.19	1.5	0.98	94	105	<0.5	<5	1.64	3	11	91	83	4.45	<1	0.20	<10	0.62	1198	6	0.01	3	755	65	1.81	<5	3	45	<5	<0.01	<10	<10	39	<10	300	2
8V3063RA/RJ	HL08-33	120127	19.72	21.05	1.33	0.39	0.9	0.90	89	87	<0.5	<5	1.73	2	11	100	73	4.17	<1	0.21	<10	0.70	1402	9	0.01	3	733	22	1.49	<5	3	66	<5	<0.01	<10	<10	34	<10	144	2
8V3063RA/RJ	HL08-33	120128	21.05	22.15	1.10	0.22	1.1	0.37	201	83	<0.5	<5	2.90	4	17	109	45	4.01	<1	0.23	<10	0.54	1735	6	0.01	4	837	20	2.69	<5	4	229	<5	<0.01	<10	<10	16	<10	60	2
8V3063RA/RJ	HL08-33	120129	22.15	23.25	1.10	1.57	7.9	0.64	205	107	<0.5	<5	3.93	7	18	105	156	5.29	<1	0.32	<10	0.65	1990	7	0.01	4	1029	39	3.19	<5	5	284	<5	<0.01	<10	<10	30	<10	464	2
8V3063RA/RJ	HL08-33	120130	23.25	25.25	2.00	0.24	1.4	1.14	144	107	<0.5	<5	4.54	3	17	71	63	4.67	<1	0.26	<10	0.63	2478	3	0.01	3	955	53	1.39	<5	5	127	<5	<0.01	<10	<10	64	<10	136	2
8V3063RA/RJ	HL08-33	120131	25.25	27.25	2.00	0.04	0.2	1.22	51	103	<0.5	<5	2.96	1	9	115	19	3.97	<1	0.21	<10	0.79	1545	4	0.01	3	788	23	0.64	<5	4	76	<5	<0.01	<10	<10	49	<10	107	2
8V3063RA/RJ	HL08-33	120132	27.25	29.25	2.00	0.09	1.0	1.11	126	106	<0.5	<5	3.12	4	9	96	41	3.93	<1	0.20	<10	0.76	1673	2	0.01	2	764	236	1.39	<5	3	82	<5	<0.01	<10	<10	46	<10	286	2
8V3063RA/RJ	HL08-33	120133	29.25	30.70	1.45	0.08	0.4	1.10	106	101	<0.5	<5	2.86	3	9	118	35	3.91	<1	0.20	<10	0.76	1597	4	0.01	3	752	125	1.47	<5	3	76	<5	<0.01	<10	<10	46	<10	242	2
8V3063RA/RJ	HL08-33	120134	30.70	31.25	0.55	0.24	5.4	0.52	233	22	<0.5	<9	0.69	7	10	100	102	>15.00	<1	0.19	<10	0.22	588	<2	<0.01	1	923	111	>5.00	35	1	26	<5	<0.01	<10	20	28	<10	598	8
8V3063RA/RJ	HL08-33	120135	31.25	33.00	1.75	0.06	1.9	0.97	47	73	<0.5	<5	2.60	1	13	90	252	3.70	<1	0.21	<10	0.45	1214	7	0.01	2	740	12	1.00	<5	3	76	<5	0.01	<10	<10	58	<10	108	2
8V3063RA/RJ	HL08-33	120136	33.00	34.70	1.70	0.10	1.4	1.08	100	73	<0.5	<5	3.35	2	13	80	194	4.06	<1	0.20	<10	0.60	1439	4	0.01	2	818	19	0.83	<5	4	121	<5	0.01	<10	<10	56	<10	112	2
8V3063RA/RJ	HL08-33	120137	34.70	36.45	1.75	0.07	0.4	1.28	24	134	<0.5	<5	2.64	<1	14	74	111	4.30	<1	0.25	<10	0.69	1250	5	0.02	3	890	8	0.62	<5	5	83	<5	0.01	<10	<10	75	<10	90	2
8V3063RA/RJ	HL08-33	120138	36.45	37.00	0.55	0.02	<0.1	0.75	<5	363	<0.5	<5	2.78	<1	8	53	11	2.08	<1	0.28	<10	0.60	648	<2	0.03	5	704	8	0.27	<5	3	138	<5	<0.01	<10	<10	23	<10	44	5
8V3063RA/RJ	HL08-33	120139	46.00	46.50	0.50	0.02	<0.1	0.76	<5	94	<0.5	<5	2.74	<1	8	50	16	2.15	<1	0.29	<10	0.61	911	<2	0.02	4	718	16	0.43	<5	3	159	<5	<0.01	<10	<10	15	<10	58	3
8V3063RA/RJ	HL08-33	120140	46.50	47.75	1.25	0.05	0.3	0.83	33	46	<0.5	<5	1.82	1	7	114	11	2.80	<1	0.18	<10	0.53	860	2	0.01	4	526	38	0.69	<5	2	89	6	<0.01	<10	<10	30	<10	64	2
8V3063RA/RJ	HL08-33	120141	47.75	49.00	1.25	0.08	0.4	1.10	38	207	<0.5	<5	2.10	1	12	112	45	3.47	<1	0.18	<10	0.59	1007	5	0.02	4	601	6	0.97	<5	3	102	7	<0.01	<10	<10	51	<10	45	2
8V3063RA/RJ	HL08-33	120142	49.00	50.55	1.55	0.03	<0.1	0.90	31	93	<0.5	<5	2.39	1	7	76	<1	2.86	<1	0.24	<10	0.52	1115	<2	0.01	1	730	24	0.88	<5	2	114	<5	<0.01	<10	<10	25	<10	100	2
8V3063RA/RJ	HL08-33	120143	50.55	52.06	1.51	0.09	<0.1	0.43	43	291	<0.5	<5	4.98	1	7	121	<1	2.72	<1	0.20	<10	0.49	2000	4	0.01	2	593	10	0.95	<5	2									

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																										
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3063RA/RJ	HL08-33	120185	114.80	116.75	1.95	0.05	0.2	0.58	105	116	<0.5	<5	3.68	2	14	24	<1	4.90	<1	0.37	<10	0.56	1346	<2	0.02	2	1261	23	3.75	<5	2	201	<5	<0.01	<10	<10	17	<10	121	3
8V3063RA/RJ	HL08-33	120186	116.75	118.70	1.95	0.02	5.7	1.86	39	197	<0.5	<5	0.91	3	15	56	3	4.77	<1	0.73	12	0.86	1152	3	0.03	3	1178	146	1.97	<5	3	58	<5	<0.01	<10	<10	49	<10	438	3
8V3063RA/RJ	HL08-33	120187	118.70	120.70	2.00	0.07	11.6	1.33	30	156	<0.5	<5	1.73	2	13	34	<1	4.31	<1	0.33	11	0.88	1528	2	0.02	2	1098	78	1.01	<5	2	89	<5	<0.01	<10	<10	43	<10	355	2
8V3063RA/RJ	HL08-33	120188	120.70	122.70	2.00	0.01	2.9	1.75	29	164	<0.5	<5	3.78	<1	14	20	<1	4.38	<1	0.37	12	0.93	1922	<2	0.03	2	1172	27	0.74	<5	3	204	<5	<0.01	<10	<10	52	<10	120	2
8V3063RA/RJ	HL08-33	120189	122.70	124.70	2.00	0.03	0.7	1.90	16	171	<0.5	<5	3.55	<1	14	23	<1	4.52	<1	0.34	12	1.05	1643	<2	0.03	2	1188	21	0.65	<5	3	216	<5	<0.01	<10	<10	52	<10	105	2
8V3063RA/RJ	HL08-33	120190	124.70	126.50	1.80	0.07	1.4	1.93	27	151	<0.5	<5	4.02	1	16	27	22	4.98	<1	0.32	<10	1.08	1637	6	0.03	2	1165	41	1.58	<5	3	158	<5	<0.01	<10	<10	59	<10	168	3
8V3063RA/RJ	HL08-33	120191	126.50	128.18	1.68	0.03	1.4	1.62	29	181	<0.5	<5	2.52	1	17	37	19	4.90	<1	0.32	<10	0.92	1292	8	0.03	3	1194	40	1.94	<5	3	100	<5	<0.01	<10	<10	48	<10	123	3
8V3063RA/RJ	HL08-33	120192	128.18	130.00	1.82	0.46	10.5	0.88	161	138	<0.5	<5	2.23	4	13	33	<1	4.64	<1	0.31	10	0.64	1370	7	0.02	2	1062	128	2.80	<5	2	110	<5	<0.01	<10	<10	28	<10	327	3
8V3063RA/RJ	HL08-33	120193	130.00	132.00	2.00	0.08	3.3	1.24	74	143	<0.5	<5	2.06	2	13	38	<1	4.36	<1	0.35	10	0.61	1393	4	0.02	2	1124	57	2.63	<5	2	91	<5	<0.01	<10	<10	31	<10	153	3
8V3063RA/RJ	HL08-33	120194	132.00	134.00	2.00	0.05	23.5	1.16	89	137	<0.5	<5	1.23	3	16	27	<1	4.58	<1	0.30	10	0.60	1208	2	0.02	2	1130	113	3.06	<5	2	67	<5	<0.01	<10	<10	33	<10	330	3
8V3063RA/RJ	HL08-33	120195	134.00	136.00	2.00	0.03	1.9	1.49	163	208	<0.5	<5	0.50	3	14	35	<1	4.18	<1	0.43	14	0.66	1142	2	0.02	2	1203	32	1.73	6	2	31	<5	<0.01	<10	<10	39	<10	142	2
8V3063RA/RJ	HL08-33	120196	136.00	138.00	2.00	0.03	2.1	1.42	91	182	<0.5	<5	1.27	2	13	26	<1	3.63	<1	0.38	11	0.72	1294	3	0.02	1	1124	20	1.06	<5	2	90	<5	<0.01	<10	<10	37	<10	108	2
8V3063RA/RJ	HL08-33	120197	138.00	139.00	1.00	0.24	2.1	0.58	316	56	<0.5	<5	0.40	6	15	44	<1	4.42	<1	0.31	<10	0.20	313	13	0.02	2	1144	37	4.76	<5	1	30	<5	<0.01	<10	<10	13	<10	111	3
8V3063RA/RJ	HL08-33	120198	139.00	140.00	1.00	0.02	23.2	1.43	34	135	<0.5	<5	0.83	2	14	14	<1	4.50	<1	0.26	10	0.93	1429	<2	0.02	1	1173	93	1.86	<5	2	49	<5	<0.01	<10	<10	40	<10	360	2
8V3063RA/RJ	HL08-33	120199	140.00	141.70	1.70	0.02	1.0	1.69	34	160	<0.5	<5	1.21	<1	13	36	<1	4.25	<1	0.31	11	1.01	1750	<2	0.03	2	1111	16	1.06	<5	2	75	<5	<0.01	<10	<10	48	<10	96	2
8V3063RA/RJ	HL08-33	120200	Blank	Blank	0.01	<0.1	0.93	<5	250	<0.5	<5	0.44	<1	9	82	<1	2.02	<1	0.47	<10	0.59	596	<2	0.05	4	764	5	<0.01	<5	2	43	<5	0.12	<10	<10	40	<10	54	2	
8V3063RA/RJ	HL08-33	120201	141.70	143.40	1.70	0.05	2.5	1.24	64	142	<0.5	<5	0.65	1	13	39	<1	4.15	<1	0.33	<10	0.69	1157	2	0.02	2	1144	19	2.29	<5	2	35	<5	<0.01	<10	<10	31	<10	108	2
8V3063RA/RJ	HL08-33	120202	143.40	144.44	1.04	0.21	9.6	0.33	307	61	<0.5	<5	0.33	6	12	82	<1	4.74	<1	0.24	<10	0.07	150	3	0.02	3	992	48	>5.00	8	1	26	<5	<0.01	<10	<10	7	<10	132	3
8V3063RA/RJ	HL08-33	120203	144.44	145.50	1.06	0.36	17.8	0.30	632	50	<0.5	<5	0.29	15	15	48	<1	5.61	<1	0.22	<10	0.09	159	2	0.02	3	1102	140	>5.00	26	1	22	<5	<0.01	<10	<10	8	<10	396	3
8V3063RA/RJ	HL08-33	120204	145.50	146.60	1.10	0.15	24.3	0.45	248	52	<0.5	<5	0.39	6	16	59	<1	4.89	<1	0.32	<10	0.13	239	4	0.02	3	1120	128	>5.00	14	1	27	<5	<0.01	<10	<10	10	<10	252	3
8V3063RA/RJ	HL08-33	120205	146.60	147.80	1.20	0.02	2.5	0.81	73	140	<0.5	<5	0.92	1	15	21	<1	4.57	<1	0.27	10	0.73	1370	3	0.02	2	1280	16	1.68	<5	2	52	<5	<0.01	<10	<10	25	<10	117	2
8V3063RA/RJ	HL08-33	120206	147.80	149.70	1.90	0.11	3.7	0.31	88	76	<0.5	<5	1.79	2	13	46	31	3.75	<1	0.23	<10	0.51	1081	5	0.01	4	920	43	2.66	<5	2	106	<5	<0.01	<10	<10	13	<10	108	2
8V3063RA/RJ	HL08-33	120207	149.70	151.70	2.00	0.03	0.5	0.45	16	161	<0.5	<5	2.71	<1	12	34	27	3.98	<1	0.24	<10	0.84	1606	<2	0.02	3	983	18	1.50	<5	2	145	<5	<0.01	<10	<10	21	<10	105	2
8V3063RA/RJ	HL08-33	120208	151.70	153.66	1.96	0.01	2.9	0.93	16	130	<0.5	<5	3.26	<1	11	32	25	3.93	<1	0.25	<10	0.80	1632	<2	0.02	2	974	32	1.42	<5	2	136	<5	<0.01	<10	<10	29	<10	94	2
HL08-34 - Zone: Snow Show, Pad 25: 435175E,622335N, Elev: 1219m, Az: 220, Dip: -50, EOH: 103.38m																																								
8V3063RA/RJ	HL08-34	120209	4.84	5.59	0.75	0.29	1.1	1.15	660	68	<0.5	<5	3.14	13	15	48	25	4.37	<1	0.16	<10	0.96	2056	5	0.01	1	971	29	2.43	<5	4	89	<5	0.01	<10	<10	68	<10	155	2
8V3063RA/RJ	HL08-34	120210	5.59	7.51	1.92	0.30	1.3	1.22	591	59	<0.5	<5	3.28	14	14	43	62	4.70	<1	0.20	<10	0.81	2169	5	0.01	1	948	73	2.43	<5	3	72	<5	0.01	<10	<10	63	<10	386	2
8V3063RA/RJ	HL08-34	120211	7.51	9.44	1.93	0.20	1.2	1.41	181	63	<0.5	<5	4.03	4	15	33	78	4.86	<1	0.17	<10	0.84	2106	4	0.01	1	1022	34	1.50	<5	5	82	<5	0.04	<10	<10	81	<10	293	2
8V3063RA/RJ	HL08-34	120212	9.44	11.35	1.91	0.11	1.7	1.41	202	78	<0.5	<5	3.01	4	17	29	139	4.82	<1	0.24	<10	0.79	1719	8	0.01	1	1118	15	1.15	<5	4	75	<5	0.03	<10	<10	65	<10	172	2
8V3063RA/RJ	HL08-34	120213	11.35	12.71	1.36	0.18	3.0	0.46	875	93	<0.5	<5	2.84	18	15	46	71	3.92	<1	0.28	<10	0.53	1606	19	0.01	2	1097	60	1.93	<5	4	204	<5	<0.01	<10	<10	20	<10	129	1
8V3063RA/RJ	HL08-34	120214	12.71	14.83	2.12	0.31	2.3	0.69	1259	97	<0.5	<5	2.98	27	17	44	95	5.04	<1	0.25	<10																			

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																												
					0.5-1.0	1.0-3.0	3.0-5.0	>5.0	5-10	10-50	50-100	>100	2500-5000	5000-10000	>10000	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Ti ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm														
8V3081RA/RJ	HL08-34	120256	85.92	86.56	0.64	<0.01	0.4	0.46	8	142	<0.5	<5	2.65	<1	9	26	10	2.40	<1	0.29	15	0.68	503	<2	0.02	3	997	19	0.18	<5	2	105	<5	<0.01	<10	<10	10	<10	58	5	
8V3081RA/RJ	HL08-34	120257	86.56	87.61	1.05	0.09	0.9	1.25	21	222	<0.5	<5	6.10	<1	11	41	148	3.89	<1	0.22	10	0.89	1790	14	0.01	2	958	10	0.38	<5	4	135	<5	0.01	<10	<10	44	<10	102	2	
8V3081RA/RJ	HL08-34	120258	87.61	89.65	2.04	0.10	1.9	2.14	39	196	<0.5	<5	3.39	2	18	45	313	5.51	<1	0.18	<10	1.60	1675	10	0.01	6	1401	63	0.74	<5	7	103	<5	0.02	<10	<10	86	<10	224	2	
8V3081RA/RJ	HL08-34	120259	89.65	91.35	1.70	0.25	1.9	2.07	1221	149	<0.5	<5	4.34	24	18	39	318	5.71	<1	0.22	<10	1.52	2100	12	0.02	5	1466	61	1.47	<5	9	81	<5	0.04	<10	<10	96	<10	232	3	
8V3081RA/RJ	HL08-34	120260	91.35	92.80	1.45	0.20	2.5	2.28	63	144	<0.5	<5	2.81	3	22	39	330	6.00	<1	0.24	<10	1.59	1685	7	0.02	4	1529	42	1.26	<5	11	61	<5	0.10	<10	<10	106	<10	247	3	
8V3081RA/RJ	HL08-34	120261	92.80	94.01	1.21	0.09	1.1	1.83	26	155	<0.5	<5	3.65	1	19	42	265	4.92	<1	0.20	<10	1.15	1438	21	0.03	6	1484	42	0.56	<5	11	90	<5	0.08	<10	<10	99	<10	188	3	
8V3081RA/RJ	HL08-34	120262	94.01	94.92	0.91	<0.01	0.1	0.80	<5	1003	<0.5	<5	3.27	<1	8	31	21	2.00	<1	0.26	17	0.70	1664	<2	0.02	5	810	5	0.13	<5	3	113	<5	<0.01	<10	<10	22	<10	48	3	
8V3081RA/RJ	HL08-34	120263	97.20	99.53	2.33	0.20	1.4	1.55	22	121	<0.5	<5	4.78	<1	20	34	223	4.58	<1	0.29	<10	1.23	1795	8	<0.01	7	1423	17	0.31	<5	7	180	<5	<0.01	<10	<10	51	<10	131	2	
8V3081RA/RJ	HL08-34	120264	99.53	101.38	1.85	0.11	1.4	1.77	21	134	<0.5	<5	3.90	1	23	33	246	5.01	<1	0.32	<10	1.24	1725	15	<0.01	7	1605	17	0.26	<5	7	161	<5	0.01	<10	<10	54	<10	193	2	
8V3081RA/RJ	HL08-34	120265	101.38	103.23	1.85	0.52	3.4	1.60	3742	109	<0.5	<5	3.07	73	22	29	310	5.67	<1	0.28	<10	0.99	1745	7	<0.01	7	1554	63	1.43	16	112	<5	<0.01	<10	<10	52	<10	295	2		
8V3081RA/RJ	HL08-34	120266	103.23	105.18	1.95	0.35	4.1	1.90	61	88	<0.5	<5	1.96	2	17	49	381	5.70	<1	0.21	<10	1.05	1515	14	<0.01	6	1294	30	1.01	<5	6	43	<5	0.01	<10	<10	78	<10	201	2	
HL08-35 - Zone: 49er, Pad 26: 435284E,6223238N, Elev: 1232m, Az: 052, Dip: -50, EOH: 163.41m																																									
8V3081RA/RJ	HL08-35	120267	1.55	3.30	1.75	<0.01	0.2	0.77	12	547	<0.5	<5	2.06	<1	8	23	14	2.27	<1	0.24	18	0.55	448	<2	0.02	3	982	29	0.09	<5	2	78	<5	<0.01	<10	<10	20	<10	99	5	
8V3081RA/RJ	HL08-35	120268	3.30	4.43	1.05	0.05	0.7	1.19	17	94	<0.5	<5	3.25	1	12	25	45	4.18	<1	0.25	10	0.95	1511	2	0.01	2	1084	38	0.52	<5	3	89	<5	<0.01	<10	<10	42	<10	205	2	
8V3081RA/RJ	HL08-35	120269	4.43	5.95	1.52	0.28	1.6	0.50	41	119	0.5	<5	2.75	1	14	29	80	4.39	<1	0.25	<10	0.63	1432	11	<0.01	3	1035	40	1.21	<5	3	89	<5	<0.01	<10	<10	22	<10	178	2	
8V3081RA/RJ	HL08-35	120270	5.95	7.20	1.25	0.42	2.3	1.62	35	79	<0.5	<5	3.04	1	18	25	163	5.47	<1	0.19	<10	0.90	1654	15	0.01	2	1401	39	1.27	<5	5	121	<5	<0.01	<10	<10	82	<10	258	2	
8V3081RA/RJ	HL08-35	120271	7.20	8.90	1.70	0.19	2.8	1.43	129	118	<0.5	<5	5.49	9	19	29	138	5.03	<1	0.27	<10	0.88	2010	10	0.02	1	1149	300	2.61	<5	4	153	<5	0.01	<10	<10	58	<10	870	2	
8V3081RA/RJ	HL08-35	120272	8.90	10.55	1.65	0.06	0.8	1.31	56	241	<0.5	<5	8.60	2	12	22	61	4.45	<1	0.23	<10	0.68	2618	7	0.01	1	1022	29	1.56	<5	4	165	<5	0.01	<10	<10	44	<10	153	2	
8V3081RA/RJ	HL08-35	120273	11.90	12.77	0.87	<0.01	0.7	0.93	<5	538	<0.5	<5	2.83	<1	8	43	7	1.97	<1	0.26	17	0.63	586	<2	0.02	5	776	10	0.03	<5	2	100	<5	<0.01	<10	<10	18	<10	71	4	
8V3081RA/RJ	HL08-35	120274	12.77	14.80	2.03	<0.01	0.6	0.49	<5	164	<0.5	<5	3.75	<1	7	28	2	1.74	<1	0.23	14	0.74	770	<2	0.02	4	719	7	0.04	<5	2	209	<5	<0.01	<10	<10	10	<10	49	3	
8V3081RA/RJ	HL08-35	120275	Std	PM1116		0.08	739.2	1.02	493	248	<0.5	<5	149	0.67	18	9	336	7021	2.82	4	0.30	<10	0.63	349	482	0.08	13	451	994	1.34	1353	2	90	<5	0.05	<10	<10	30	<10	1029	3
8V3081RA/RJ	HL08-35	120276	23.00	23.52	0.52	<0.01	1.0	0.88	<5	632	<0.5	<5	3.57	<1	8	26	23	1.91	<1	0.24	15	0.70	670	3	0.02	5	786	6	0.13	<5	2	188	<5	<0.01	<10	<10	19	<10	56	3	
8V3081RA/RJ	HL08-35	120277	23.52	24.75	1.23	0.22	2.0	0.99	111	78	<0.5	<5	4.49	8	13	100	120	4.24	<1	0.30	<10	0.69	1608	14	0.02	4	850	413	2.32	<5	3	261	<5	<0.01	<10	<10	32	<10	738	2	
8V3081RA/RJ	HL08-35	120278	24.75	25.90	1.15	0.63	2.2	1.58	117	157	<0.5	<5	3.46	4	16	41	149	5.34	<1	0.27	<10	0.89	1820	41	0.02	2	1236	31	2.23	<5	4	145	<5	<0.01	<10	<10	57	<10	421	3	
8V3081RA/RJ	HL08-35	120279	25.90	26.72	0.82	0.36	1.5	0.57	219	47	<0.5	<5	12.63	5	10	76	48	4.17	<1	0.22	<10	0.30	2939	8	0.01	2	713	89	4.14	<5	2	230	<5	<0.01	<10	13	<10	159	1		
8V3081RA/RJ	HL08-35	120280	26.72	28.20	1.48	0.30	3.8	1.25	134	78	<0.5	<5	3.56	4	15	81	286	4.98	<1	0.27	<10	0.64	1774	9	0.02	4	1085	92	2.59	<5	3	139	<5	<0.01	<10	<10	58	<10	333	2	
8V3081RA/RJ	HL08-35	120281	28.20	29.68	1.48	0.34	2.6	1.74	318	93	<0.5	<5	3.24	7	19	31	168	6.39	<1	0.31	<10	0.96	2001	18	0.01	2	1409	36	3.03	<5	4	106	<5	<0.01	<10	11	66	<10	288	2	
8V3081RA/RJ	HL08-35	120282	29.68	31.74	2.06	0.24	1.6	0.99	336	112	<0.5	<5	3.88	7	12	85	79	4.53	<1	0.20	<10	0.67	1944	12	0.01	3	812	67	3.11	<5	2	108	<5	<0.01	<10	<10	43	<10	180	2	
8V3081RA/RJ	HL08-35	120283	31.74	33.70	1.96	0.52	2.3	2.10	262	112	<0.5	<5	3.36	5	16	17	191	5.70	<1	0.29	<10	1.29	2300	20	0.02	<1	1398	28	1.43	<5	4	112	<5	0.03	<10	11	77	<10	224	2	
8V3081RA/RJ	HL08-35	120284	33.70	35.70	2.00	0.51	1.8	1.99	60	113	<0.5	<5	4.52	2	16	26	197	5.25	<1	0.31	10	1.11	2436	12	0.02	<1	1376	63	0.92	<5	4	151	<5	0.10	<10	11	75	<10	337	2	
8V3081RA/RJ	HL08-35	120285	35.70	37.70	2.00	0.67	3.9	2.02	103	93	<0.5	<5	3.67	3	19	13	350	5.67	<1	0.27	<10	1.26	2285	21	0.02	<1	1348	18	1.39	<5	5	123	<5	0.14	<10	11	85	<1			

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3081RA/RJ	HL08-35	120327	105.00	107.00	2.00	0.24	1.3	1.83	10	99	<0.5	<5	2.09	1	19	23	130	4.75	<1	0.18	<10	1.14	1079	10	0.02	1	1110	29	0.36	<5	6	67	<5	0.12	<10	<10	97	<10	161	2
8V3081RA/RJ	HL08-35	120328	107.00	109.00	2.00	0.25	0.9	1.94	19	105	<0.5	<5	2.67	1	20	14	98	4.98	<1	0.25	<10	1.07	1256	7	0.02	1	1187	12	0.51	<5	5	70	<5	0.10	<10	<10	91	<10	164	2
8V3081RA/RJ	HL08-35	120329	109.00	111.05	2.05	0.26	1.0	1.89	<5	64	<0.5	<5	2.28	1	20	28	95	4.50	<1	0.14	<10	1.14	1305	8	0.02	1	1086	14	0.27	<5	4	83	<5	0.16	<10	<10	87	<10	202	3
8V3081RA/RJ	HL08-35	120330	111.05	112.95	1.90	0.26	1.2	1.61	11	76	<0.5	<5	3.06	1	15	24	70	4.00	<1	0.19	<10	0.97	1531	3	0.02	2	955	38	0.41	<5	5	76	<5	0.12	<10	<10	63	<10	183	3
8V3081RA/RJ	HL08-35	120331	112.95	114.85	1.90	0.35	1.8	1.82	33	120	<0.5	<5	4.12	2	17	21	136	4.75	<1	0.23	<10	0.98	2172	8	0.01	1	1030	23	0.63	<5	5	102	<5	0.07	<10	<10	76	<10	194	2
8V3081RA/RJ	HL08-35	120332	114.85	116.75	1.90	0.24	2.8	1.88	62	114	<0.5	<5	4.33	5	20	15	207	5.39	<1	0.28	<10	0.94	2331	5	0.01	<1	1136	17	1.17	<5	6	115	<5	0.07	<10	<10	98	<10	280	2
8V3081RA/RJ	HL08-35	120333	116.75	118.65	1.90	0.24	1.8	1.60	224	108	<0.5	<5	3.93	6	15	31	119	4.39	<1	0.24	<10	0.89	2055	5	0.02	1	991	16	0.90	<5	5	103	<5	0.07	<10	<10	76	<10	243	2
8V3081RA/RJ	HL08-35	120334	118.65	120.00	1.35	0.41	18.8	0.94	188	89	<0.5	<5	5.00	8	11	29	54	5.00	<1	0.25	<10	0.54	1942	12	<0.01	1	797	272	3.82	<5	3	129	<5	<0.01	<10	<10	29	<10	576	2
8V3081RA/RJ	HL08-35	120335	120.00	122.00	2.00	0.24	1.2	0.82	85	377	<0.5	<5	3.38	3	11	36	76	3.93	<1	0.30	<10	0.86	1586	12	0.01	1	908	31	0.49	<5	4	216	<5	<0.01	<10	<10	20	<10	189	1
8V3081RA/RJ	HL08-35	120336	122.00	124.00	2.00	0.32	1.0	1.49	15	194	<0.5	<5	2.54	1	11	35	60	4.28	<1	0.29	<10	0.98	1329	6	0.02	1	970	33	0.48	<5	5	111	<5	0.01	<10	<10	45	<10	172	2
8V3081RA/RJ	HL08-35	120337	124.00	126.00	2.00	0.32	1.0	1.44	13	161	<0.5	<5	2.68	1	11	42	58	4.22	<1	0.29	<10	0.87	1365	26	0.01	1	944	11	0.61	<5	5	88	<5	0.01	<10	<10	53	<10	186	1
8V3081RA/RJ	HL08-35	120338	126.00	128.00	2.00	0.27	0.9	1.50	21	107	<0.5	<5	2.33	1	10	40	60	4.33	<1	0.22	<10	0.84	1213	13	0.02	1	864	12	0.86	<5	5	71	<5	0.01	<10	<10	59	<10	155	2
8V3081RA/RJ	HL08-35	120339	128.00	130.00	2.00	0.37	1.3	1.49	24	88	<0.5	<5	2.92	1	11	42	65	4.24	<1	0.23	<10	0.84	1252	7	0.01	1	907	37	0.73	<5	4	110	<5	<0.01	<10	<10	52	<10	157	1
8V3081RA/RJ	HL08-35	120340	130.00	132.00	2.00	0.35	1.2	1.37	49	128	<0.5	<5	2.68	1	10	41	67	4.08	<1	0.25	<10	0.78	1331	6	0.01	1	874	15	1.17	<5	4	95	<5	<0.01	<10	<10	47	<10	149	1
8V3081RA/RJ	HL08-35	120341	132.00	133.60	1.60	0.29	1.7	1.26	38	134	<0.5	<5	2.68	1	11	44	79	3.89	<1	0.28	<10	0.78	1624	5	<0.01	1	942	15	1.16	<5	4	122	<5	<0.01	<10	<10	43	<10	150	1
8V3081RA/RJ	HL08-35	120342	133.60	134.60	1.00	0.41	3.9	0.68	188	108	<0.5	<5	2.03	10	11	48	88	4.44	<1	0.26	<10	0.59	1292	12	<0.01	1	788	753	3.03	<5	3	133	<5	<0.01	<10	<10	22	<10	890	1
8V3081RA/RJ	HL08-35	120343	134.60	135.60	1.00	0.43	1.5	1.09	48	91	<0.5	<5	3.67	4	10	41	99	3.84	<1	0.20	<10	0.75	1989	4	0.01	1	868	31	1.39	<5	3	118	<5	<0.01	<10	<10	42	<10	504	2
8V3081RA/RJ	HL08-35	120344	135.60	136.60	1.00	0.20	0.4	1.09	51	185	<0.5	<5	2.32	1	11	57	38	4.33	<1	0.27	<10	0.70	1346	3	0.01	1	971	13	1.84	<5	3	93	<5	<0.01	<10	<10	43	<10	139	2
8V3081RA/RJ	HL08-35	120345	136.60	138.60	2.00	0.39	0.9	1.20	28	90	<0.5	<5	2.21	1	11	48	90	4.46	<1	0.20	<10	0.76	1242	15	0.02	1	955	12	1.52	<5	4	76	<5	0.01	<10	<10	50	<10	188	2
8V3081RA/RJ	HL08-35	120346	138.60	139.60	1.00	0.24	2.0	0.75	180	89	<0.5	<5	5.08	4	11	42	47	5.45	<1	0.25	<10	0.49	1753	8	0.01	1	960	123	>5.00	<5	3	196	<5	<0.01	<10	<10	26	<10	180	2
8V3081RA/RJ	HL08-35	120347	139.60	141.33	1.73	0.24	1.5	0.97	106	171	<0.5	<5	3.88	3	13	51	119	4.43	<1	0.31	<10	0.75	1976	6	0.01	1	1115	36	1.71	<5	3	217	<5	<0.01	<10	<10	35	<10	225	2
8V3081RA/RJ	HL08-35	120348	141.33	143.05	1.72	0.18	1.2	0.48	116	157	<0.5	<5	3.76	3	12	55	69	4.23	<1	0.33	<10	0.65	1743	13	0.01	1	1047	35	2.71	<5	3	173	<5	<0.01	<10	<10	13	<10	193	2
8V3081RA/RJ	HL08-35	120349	143.05	144.80	1.75	0.12	0.5	0.44	66	180	<0.5	<5	2.94	1	12	46	51	4.18	<1	0.32	<10	0.70	1564	4	0.01	1	1040	32	1.83	<5	3	141	<5	<0.01	<10	<10	15	<10	131	2
8V3081RA/RJ	HL08-35	120350	Blank	Blank		0.01	<0.1	1.01	<5	348	<0.5	<5	0.53	<1	12	130	3	2.42	<1	0.51	<10	0.69	741	<2	0.06	7	846	8	0.02	<5	3	50	5	0.14	<10	<10	48	<10	72	2
8V3081RA/RJ	HL08-35	120351	144.80	146.00	1.20	0.03	<0.1	0.46	5	204	<0.5	<5	2.72	<1	8	65	2	2.14	<1	0.35	<10	0.71	586	<2	0.03	4	833	22	0.08	<5	2	155	<5	<0.01	<10	<10	11	<10	53	4
8V3081RA/RJ	HL08-35	120352	146.00	147.50	1.50	0.01	<0.1	0.31	5	1259	<0.5	<5	3.10	<1	7	57	1	2.18	<1	0.29	<10	0.84	526	<2	0.03	4	754	9	0.11	<5	2	211	<5	<0.01	<10	<10	6	<10	42	3
8V3081RA/RJ	HL08-35	120353	153.00	154.33	1.33	0.01	<0.1	0.94	<5	1307	<0.5	<5	2.14	<1	9	57	7	2.29	<1	0.25	<10	0.78	535	<2	0.04	5	784	29	0.07	<5	3	99	<5	0.01	<10	<10	31	<10	49	6
8V3081RA/RJ	HL08-35	120354	154.33	155.30	0.97	0.21	0.2	1.97	6	220	<0.5	<5	4.43	<1	15	29	94	5.26	<1	0.32	<10	1.04	1831	6	0.05	1	1271	26	0.33	<5	7	96	<5	0.01	<10	<10	105	<10	153	2
8V3081RA/RJ	HL08-35	120355	155.30	156.30	1.00	0.28	1.1	1.88	13	108	<0.5	<5	3.60	1	17	35	186	5.10	<1	0.29	<10	1.05	1751	11	0.03	1	1326	38	0.66	<5	6	130	<5	0.01	<10	<10	98	<10	207	2
8V3081RA/RJ	HL08-35	120356	156.30	158.00	1.70	0.58	1.8	1.95	18	111	<0.5	<5	2.73	1	23	27	239	5.44	<1	0.17	<10	1.16	1919	21	0.04	<1	1232	46	0.97	<5										

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0					Ag: 5-10 10-50 50-100 >100					Pb/Zn: 2500-5000 5000-10000 >10000																									
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3100RA/RJ	HLO8-36	120403	64.25	66.18	1.93	<0.01	0.7	2.08	24	171	<0.5	<5	4.51	<1	19	10	25	4.58	<1	0.23	<10	1.14	1408	<2	<0.01	1	1219	3	0.60	<5	3	129	<5	0.04	<10	<10	27	<10	94	1
8V3100RA/RJ	HLO8-36	120404	66.18	68.18	2.00	<0.01	0.4	2.16	8	1470	<0.5	<5	4.36	<1	16	14	22	4.68	<1	0.24	<10	1.12	1362	<2	<0.01	1	1272	2	0.19	<5	3	865	<5	0.01	<10	<10	27	<10	101	1
8V3100RA/RJ	HLO8-36	120405	68.18	70.17	1.99	0.01	0.4	2.09	<5	1293	<0.5	<5	4.43	<1	16	8	19	4.81	<1	0.23	<10	1.04	1338	<2	<0.01	1	1240	3	0.22	<5	3	469	<5	0.02	<10	<10	28	<10	101	1
8V3100RA/RJ	HLO8-36	120406	70.17	72.10	1.93	0.01	0.5	2.12	7	472	<0.5	<5	5.05	<1	17	10	11	4.94	<1	0.20	<10	1.04	1527	<2	<0.01	1	1215	3	0.43	<5	3	221	<5	0.01	<10	<10	29	<10	102	1
8V3100RA/RJ	HLO8-36	120407	72.10	73.79	1.69	<0.01	0.8	1.94	17	147	<0.5	<5	3.41	<1	16	10	13	4.66	<1	0.25	<10	0.99	1359	<2	<0.01	1	1141	36	0.92	<5	3	123	<5	0.01	<10	<10	27	<10	125	1
8V3100RA/RJ	HLO8-36	120408	73.79	75.79	2.00	0.05	1.0	2.04	29	120	<0.5	<5	0.87	<1	20	19	21	6.04	<1	0.22	<10	1.04	1108	<2	<0.01	1	1336	11	2.42	<5	3	31	<5	0.01	<10	<10	30	<10	120	2
8V3100RA/RJ	HLO8-36	120409	75.79	77.79	2.00	0.13	7.0	2.07	130	141	<0.5	<5	2.60	3	22	22	23	8.78	<1	0.26	<10	1.08	1242	<2	<0.01	2	1634	34	3.71	<5	3	60	<5	0.01	<10	<10	32	<10	188	3
8V3100RA/RJ	HLO8-36	120410	77.79	79.98	2.19	0.19	2.3	2.34	147	174	<0.5	<5	1.47	2	21	23	22	7.92	<1	0.27	<10	1.20	1304	<2	<0.01	2	1631	17	2.08	<5	3	45	<5	0.01	<10	<10	41	<10	131	2
8V3100RA/RJ	HLO8-36	120411	79.98	81.98	2.00	0.04	1.4	2.83	57	152	<0.5	<5	1.78	1	21	28	17	8.30	<1	0.25	<10	1.57	1533	<2	<0.01	2	1479	8	1.10	<5	4	51	<5	0.01	<10	<10	45	<10	135	2
8V3100RA/RJ	HLO8-36	120412	81.98	83.28	1.30	0.06	1.4	2.96	113	134	<0.5	<5	4.19	2	21	19	17	8.66	<1	0.22	<10	1.68	1876	<2	<0.01	2	1633	7	1.17	<5	4	95	<5	0.01	<10	<11	42	<10	146	3
8V3100RA/RJ	HLO8-36	120413	83.28	85.06	1.78	0.03	1.1	2.65	113	162	<0.5	<5	2.21	2	19	21	21	8.04	<1	0.25	<10	1.47	1531	<2	<0.01	1	1519	6	1.21	<5	3	53	<5	0.01	<10	<10	37	<10	129	2
8V3100RA/RJ	HLO8-36	120414	85.06	87.01	1.95	0.02	0.7	2.74	144	153	<0.5	<5	1.33	2	22	19	18	7.84	<1	0.24	<10	1.49	1562	<2	<0.01	2	1588	6	0.75	<5	4	40	<5	<0.01	<10	<10	44	<10	134	2
8V3100RA/RJ	HLO8-36	120415	87.01	89.01	2.00	0.01	1.0	2.83	87	159	<0.5	<5	1.72	1	20	20	19	8.57	<1	0.23	<10	1.62	1804	<2	<0.01	1	1613	6	1.29	<5	4	48	<5	<0.01	<10	<10	44	<10	145	3
8V3100RA/RJ	HLO8-36	120416	89.01	90.98	1.97	0.01	1.1	2.62	93	145	<0.5	<5	2.25	1	22	14	23	8.41	<1	0.23	<10	1.54	1667	<2	<0.02	1	1592	7	1.69	<5	4	58	<5	0.01	<10	<10	43	<10	131	2
8V3100RA/RJ	HLO8-36	120417	90.98	92.97	1.99	0.02	1.1	2.55	191	173	<0.5	<5	3.13	3	21	19	18	7.89	<1	0.26	<10	1.34	1726	<2	<0.01	1	1596	6	1.10	<5	4	72	<5	0.01	<10	<10	43	<10	126	2
8V3100RA/RJ	HLO8-36	120418	92.97	94.88	1.91	0.07	1.6	2.33	149	171	<0.5	<5	4.74	2	20	25	16	9.03	<1	0.23	<10	1.32	2168	<2	<0.01	1	1669	14	2.99	<5	4	123	<5	<0.01	<10	13	41	<10	128	3
8V3100RA/RJ	HLO8-36	120419	94.88	96.88	2.00	0.04	1.3	2.51	102	175	<0.5	<5	2.00	1	19	20	19	8.62	<1	0.23	<10	1.39	1574	<2	<0.01	1	1486	9	1.88	<5	3	59	<5	<0.01	<10	<10	38	<10	129	2
8V3100RA/RJ	HLO8-36	120420	96.88	97.94	1.06	0.10	2.7	2.15	241	148	<0.5	<5	5.46	4	19	25	20	8.50	<1	0.21	<11	1.18	2100	<2	<0.01	1	1380	17	3.01	<5	3	116	<5	<0.01	<10	11	31	<10	111	2
8V3100RA/RJ	HLO8-36	120421	97.94	99.94	2.00	0.40	1.4	2.15	266	169	<0.5	<5	3.24	5	18	22	20	7.92	<1	0.23	<10	1.18	1608	<2	<0.01	2	1490	11	2.35	<5	3	83	<5	<0.01	<10	<10	36	<10	119	2
8V3100RA/RJ	HLO8-36	120422	99.94	101.93	1.99	0.09	3.6	2.29	470	159	<0.5	<5	1.46	9	21	25	20	8.85	<1	0.22	<10	1.28	1446	<2	<0.01	2	1378	15	2.57	5	3	63	<5	<0.01	<10	<10	39	<10	125	2
8V3100RA/RJ	HLO8-36	120423	101.93	103.87	1.94	0.03	1.4	2.84	247	201	<0.5	<5	2.93	4	22	19	23	8.78	<1	0.25	<10	1.60	1808	<2	<0.01	2	1798	7	1.22	<5	4	86	<5	<0.01	<10	10	47	<10	147	3
8V3100RA/RJ	HLO8-36	120424	103.87	105.79	1.92	0.08	1.6	2.67	211	191	<0.5	<5	3.23	4	20	22	30	8.51	<1	0.25	<10	1.55	1771	<2	<0.01	2	1854	8	1.54	<5	4	83	<5	<0.01	<10	<10	44	<10	141	3
8V3100RA/RJ	HLO8-36	120425	Blank	Blank	<0.01	<0.1	1.25	<5	333	<0.5	<5	0.75	<1	11	114	2	3.59	<1	0.56	<10	0.88	764	<2	<0.07	7	1010	5	<0.01	<5	3	55	5	0.16	<10	<10	51	<10	78	2	
8V3100RA/RJ	HLO8-36	120426	105.79	107.79	2.00	0.13	1.9	2.57	323	182	<0.5	<5	4.28	6	21	20	32	8.83	<1	0.24	<10	1.51	1866	<2	<0.01	2	1756	13	2.10	<5	4	109	<5	<0.01	<10	11	43	<10	137	3
8V3100RA/RJ	HLO8-36	120427	107.79	109.62	1.83	0.03	1.4	3.02	102	192	<0.5	<5	5.96	1	21	19	26	9.77	<1	0.26	<10	1.74	2019	<2	0.02	2	1920	10	1.97	<5	4	139	<5	<0.01	<10	12	49	<10	141	3
8V3100RA/RJ	HLO8-36	120428	109.62	111.45	1.83	0.02	1.3	3.26	94	210	<0.5	<5	6.48	1	22	20	27	9.30	<1	0.27	<10	1.92	2226	<2	0.02	2	1847	7	0.89	<5	5	158	<5	<0.01	<10	12	51	<10	156	3
8V3100RA/RJ	HLO8-36	120429	111.45	112.87	1.42	0.08	1.4	2.85	125	201	<0.5	<5	7.25	2	20	16	18	8.63	<1	0.27	<10	1.69	2246	<2	0.02	1	1772	9	1.52	<5	4	168	<5	<0.01	<10	12	42	<10	134	2
8V3100RA/RJ	HLO8-36	120430	112.87	114.78	1.91	0.03	1.8	3.58	152	175	<0.5	<5	1.87	2	25	19	27	10.25	<1	0.23	<10	2.37	1942	<2	<0.01	2	1800	10	1.18	<5	5	63	<5	<0.01	<10	11	64	<10	200	3
8V3100RA/RJ	HLO8-36	120431	114.78	116.38	1.60	0.03	1.6	2.86	187	490	<0.5	<5	0.91	3	24	35	33	7.64	<1	0.22	<10	1.92	1656	<2	<0.01	6	1490	11	1.21	<5	4	48	<5	0.01	<10	<10	62	<10	152	3
8V3100RA/RJ	HLO8-36	120432	116.38	117.89	1.51	0.02	1.1	2.91	95	187	<0.5	<5	2.29	1	25	19	30	8.15	<1	0.26	<10	1.87	1927	<2	<0.01	4	1599	13	1.21	<5	4	75	<5	0.01	<10	<10	56	<10	138	2
8V3100RA/RJ	HLO8-36	120433	117.89	119.03	1.14	0.04	1.4	2.47	339	176	<0.5	<5	2.06	6	21	29	28	7.71	<1	0.24	<10	1.46	1705	<2	<0.01	4	1310	12	1.59	<5	4	61	<5	0.02	<10	<10	47	<10	114	2
8V3100RA/RJ	HLO8-36	120434	119.03	121.03	2.00	0.24	3.7	1.75	435	158	<0.5	<5	1.04	10	21	25	22	7.34	<1	0.27	<10	0.92	1066	3	0.01	2	1360	103	3.16	6	3	43	<5	<0.01	<10	<10	34	<10	454	2
8V3100RA/RJ	HLO8-36	120435	121.03	122.92	1.89	0.24	3.3	2.17	175	175	<0.5	<5	1.33	4	22	34	44	7.28	<1	0.27	<10	1.16	1459	2	0.01	2	1673	72	1.84	<5	3	45	<5	<0.01	<10	<10	40	<10	266	2
8V3100RA/RJ	HLO8-36	120436	122.92	124.92	2.00	0.15	3.2	1.94	172	203	<0.5																													

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3100RA/RJ	HLO8-36	120475	Blank	Blank	<0.01	<0.1	0.94	<5	218	0.7	<5	0.43	1	7	89	<1	1.91	<1	0.47	<10	0.57	527	<2	0.06	5	720	2	0.01	<5	2	56	5	0.13	<10	<10	38	<10	46	3	
8V3100RA/RJ	HLO8-36	120476	190.01	191.92	1.91	0.01	0.8	1.28	93	125	<0.5	<5	2.08	2	14	14	28	3.80	<1	0.33	<10	0.66	3061	<2	0.01	3	1134	13	1.05	6	1	790	<5	<0.01	<10	<10	29	<10	86	3
8V3100RA/RJ	HLO8-36	120477	191.92	193.90	1.98	0.03	0.9	1.51	78	158	<0.5	<5	2.01	2	14	11	25	4.26	<1	0.30	<10	0.74	1402	<2	0.01	3	1288	9	1.09	5	2	96	<5	<0.01	<10	<10	38	<10	80	3
8V3100RA/RJ	HLO8-36	120478	193.90	195.90	2.00	0.04	1.1	1.63	91	120	<0.5	<5	0.73	2	16	10	39	4.60	<1	0.33	<10	0.80	1110	<2	0.01	3	1331	16	1.46	<5	1	51	<5	<0.01	<10	<10	42	<10	114	3
8V3100RA/RJ	HLO8-36	120479	195.90	197.90	2.00	0.01	1.3	1.76	63	137	<0.5	<5	1.44	2	15	7	30	4.55	<1	0.28	<10	0.94	1416	<2	0.01	2	1361	7	0.94	<5	2	88	<5	<0.01	<10	<10	47	<10	86	3
8V3100RA/RJ	HLO8-36	120480	197.90	199.85	1.95	0.01	0.3	1.60	71	172	<0.5	<5	2.34	1	14	9	28	4.02	<1	0.30	<10	0.95	1551	<2	0.01	2	1302	9	0.71	<5	2	176	<5	<0.01	<10	<10	41	<10	62	3
8V3100RA/RJ	HLO8-36	120481	199.85	201.85	2.00	<0.01	0.3	1.72	47	107	<0.5	<5	2.56	1	15	8	27	4.40	<1	0.26	<10	1.00	1502	<2	0.02	3	1314	10	1.17	<5	2	136	<5	<0.01	<10	<10	48	<10	64	3
8V3100RA/RJ	HLO8-36	120482	201.85	203.85	2.00	0.01	0.2	1.81	41	123	<0.5	<5	2.32	2	15	13	26	4.60	<1	0.22	<10	1.14	1578	<2	0.02	2	1291	7	1.14	<5	2	179	<5	<0.01	<10	<10	51	<10	80	3
8V3100RA/RJ	HLO8-36	120483	203.85	205.70	1.85	0.01	0.5	1.89	42	104	<0.5	<5	1.36	2	18	5	35	5.13	<1	0.23	<10	1.21	1284	<2	0.02	2	1394	9	1.62	<5	2	76	<5	0.01	<10	<10	58	<10	97	4
8V3100RA/RJ	HLO8-36	120484	205.70	207.70	2.00	0.01	<0.1	1.91	66	94	<0.5	<5	3.13	2	18	9	28	5.75	<1	0.23	<10	1.24	1844	<2	0.02	3	1341	5	2.46	<5	2	154	<5	0.01	<10	<10	56	<10	94	4
8V3100RA/RJ	HLO8-36	120485	207.70	209.53	1.83	0.01	0.3	1.55	67	97	<0.5	<5	3.53	2	15	5	38	4.74	<1	0.22	<10	0.96	1679	<2	0.02	2	1335	8	1.97	<5	2	182	<5	<0.01	<10	<10	47	<10	93	4
8V3100RA/RJ	HLO8-36	120486	209.53	211.49	1.96	<0.01	0.4	1.91	79	114	<0.5	<5	2.27	2	16	9	28	4.86	<1	0.24	<10	1.10	1347	<2	0.02	2	1319	8	0.98	<5	2	97	<5	<0.01	<10	<10	50	<10	71	3
8V3100RA/RJ	HLO8-36	120487	211.49	212.73	1.24	0.05	1.4	1.84	329	154	<0.5	<5	2.21	2	18	10	29	5.16	<1	0.40	<10	0.90	1166	<2	0.01	3	1569	15	1.87	9	2	102	<5	0.01	<10	<10	41	<10	47	4
8V3100RA/RJ	HLO8-36	120488	212.73	213.67	0.94	0.01	0.2	1.85	42	136	<0.5	<5	3.80	1	14	9	27	4.18	<1	0.31	<10	0.97	1496	<2	0.02	2	1367	3	0.52	<5	2	140	<5	0.01	<10	<10	38	<10	50	3
8V3100RA/RJ	HLO8-36	120489	213.67	215.64	1.97	0.10	0.7	1.18	102	118	<0.5	<5	4.84	1	13	15	25	3.48	<1	0.29	<10	0.55	1762	<2	0.01	2	1081	12	1.54	<5	1	128	<5	0.01	<10	<10	25	<10	42	3
8V3100RA/RJ	HLO8-36	120490	215.64	216.90	1.26	0.12	1.1	0.87	164	118	<0.5	<5	3.50	1	13	26	15	3.54	<1	0.32	<10	0.38	1147	<2	0.01	2	1112	27	2.64	<5	1	132	<5	0.01	<10	<10	19	<10	70	3
8V3100RA/RJ	HLO8-36	120491	216.90	218.17	1.27	0.03	0.6	1.49	98	138	<0.5	<5	4.20	2	16	12	34	4.23	<1	0.34	<10	0.82	1699	<2	0.01	2	1379	11	1.99	<5	2	155	<5	<0.01	<10	<10	30	<10	83	3
8V3100RA/RJ	HLO8-36	120492	218.17	220.14	1.97	0.06	1.0	1.54	110	97	<0.5	<5	1.88	3	16	18	46	5.01	<1	0.31	<10	0.87	1256	<2	0.02	2	1303	70	2.65	<5	2	76	<5	<0.01	<10	<10	41	<10	218	4
8V3100RA/RJ	HLO8-36	120493	220.14	222.14	2.00	0.01	0.2	1.80	40	86	<0.5	<5	1.77	2	15	7	31	4.61	<1	0.21	<10	1.13	1370	<2	0.02	2	1341	11	1.16	<5	2	82	<5	0.01	<10	<10	58	<10	83	3
8V3100RA/RJ	HLO8-36	120494	222.14	224.15	2.01	0.01	0.2	1.73	39	115	<0.5	<5	2.08	2	15	12	43	4.36	<1	0.29	<10	1.04	1314	<2	0.02	2	1397	14	1.19	<5	2	100	<5	0.01	<10	<10	50	<10	129	3
8V3100RA/RJ	HLO8-36	120495	224.15	226.16	2.01	0.02	<0.1	1.60	18	127	<0.5	<5	3.88	2	14	6	37	3.80	<1	0.22	<10	0.91	1509	<2	0.02	2	1267	30	0.54	<5	2	175	<5	0.04	<10	<10	51	<10	124	3
8V3100RA/RJ	HLO8-36	120496	226.16	228.16	2.00	0.03	<0.1	1.45	62	96	<0.5	<5	5.30	2	14	10	24	4.00	<1	0.25	<10	0.84	1826	<2	0.02	2	1263	13	1.36	<5	2	197	<5	0.02	<10	<10	40	<10	68	3
8V3100RA/RJ	HLO8-36	120497	228.16	230.10	1.94	0.01	0.3	1.69	33	96	<0.5	<5	4.42	1	15	6	23	4.29	<1	0.29	<10	0.90	1669	<2	0.02	2	1411	7	0.83	<5	3	162	<5	0.01	<10	<10	53	<10	70	3
8V3100RA/RJ	HLO8-36	120498	230.10	232.06	1.96	0.01	<0.1	1.70	18	102	<0.5	<5	4.61	1	16	8	28	3.94	<1	0.26	<10	0.97	1624	<2	0.02	2	1327	11	0.49	<5	3	163	<5	0.03	<10	<10	53	<10	77	3
HLO8-37 - Zone: Snow Show, Pad 28: 435053E,6223292N, Elev: 1173m, Az: 358, Dip: -60, EOH: 236.59m																																								
8V3100RA/RJ	HLO8-37	120499	2.13	5.00	2.87	0.45	2.8	1.11	15	80	0.7	<5	2.28	2	15	87	325	2.88	<1	0.11	<10	0.98	960	23	0.02	14	1326	18	0.13	<5	5	79	<5	0.13	<10	<10	78	<10	193	10
8V3100RA/RJ	HLO8-37	120500	Blank	Blank	<0.01	<0.1	0.97	<5	223	0.7	<5	0.44	1	7	89	<1	1.96	<1	0.50	<10	0.60	552	<2	0.07	5	755	<2	0.01	<5	2	55	<5	0.13	<10	<10	38	<10	46	3	
8V3100RA/RJ	HLO8-37	120501	5.00	7.00	2.00	0.12	2.4	1.30	22	48	0.5	<5	2.27	3	20	132	279	3.09	<1	0.08	<10	1.15	768	63	0.23	20	1436	8	0.23	<5	5	134	<5	0.13	<10	<10	95	<10	196	6
8V3100RA/RJ	HLO8-37	120502	7.00	9.00	2.00	0.11	15.3	1.22	26	48	<0.5	<5	3.37	2	17	131	172	2.72	<1	0.07	<10	1.11	910	85	0.02	19	1374	7	0.21	<5	5	92	<5	0.12	<10	<10	80	<10	146	7
8V3100RA/RJ	HLO8-37	120503	9.00	10.00	1.00	0.11	1.0	0.59	12	46	<0.5	<5	1.59	2	10	71	121	1.17	<1	0.07	<10	0.44	343	39	0.03	10	1320	7	0.03	<5	2	77	<5	0.09	<10	<10	32	<10	113	6
8V3100RA/RJ	HLO8-37	120504	10.00	12.00	2.00	0.10	0.8	0.68	15	42	<0.5	<5	2.20	1	11	75	72	1.43	<1	0.08	<10	0.46	409	107	0.03	11	1403	9	0.05	<5	2									

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3190RA/RJ	HL08-37	120546	75.00	77.00	2.00	0.19	2.1	1.10	12	68	<0.5	<5	2.08	12	15	106	268	2.17	<1	0.10	<10	0.96	732	51	0.03	16	1382	419	0.20	<5	3	62	<5	0.11	<10	<10	70	<10	1430	7
8V3190RA/RJ	HL08-37	120547	77.00	79.00	2.00	0.26	2.2	1.28	18	46	<0.5	<5	1.73	2	20	127	401	2.76	<1	0.07	<10	1.24	621	188	0.03	23	1424	7	0.20	<5	2	75	<5	0.13	<10	<10	76	<10	184	5
8V3190RA/RJ	HL08-37	120548	79.00	81.00	2.00	0.51	2.3	0.93	14	73	<0.5	<5	1.73	2	13	88	434	1.62	<1	0.13	<10	0.86	537	50	0.03	15	1415	11	0.07	<5	2	66	<5	0.12	<10	<10	50	<10	127	5
8V3190RA/RJ	HL08-37	120549	81.00	82.15	1.15	0.24	0.8	1.34	14	54	<0.5	<5	4.53	2	15	127	209	2.59	<1	0.07	<10	1.34	1558	32	0.02	19	1409	44	0.05	<5	5	117	<5	0.11	<10	<10	80	24	131	9
8V3190RA/RJ	HL08-37	120550	Blank	Blank	0.01	<0.1	1.01	1.41	<5	237	0.7	<5	0.52	1	7	112	2	2.10	<1	0.51	<10	0.62	571	2	0.07	7	693	2	<0.01	<5	2	62	<5	0.14	<10	<10	41	<10	54	3
8V3190RA/RJ	HL08-37	120551	82.15	83.80	1.65	0.12	2.3	1.47	17	44	<0.5	<5	6.79	3	19	171	207	3.23	<1	0.08	<10	1.29	2215	26	0.02	25	1446	310	0.12	<5	10	125	<5	0.11	<10	<10	115	<10	255	9
8V3190RA/RJ	HL08-37	120552	83.80	85.10	1.30	0.05	0.3	2.24	18	26	<0.5	<5	10.43	2	19	219	153	4.74	<1	0.03	<10	1.96	3361	23	0.01	30	1239	17	0.08	<5	15	201	<5	0.09	<10	<10	158	34	116	6
8V3190RA/RJ	HL08-37	120553	85.10	86.70	1.60	0.14	0.2	1.52	14	41	<0.5	<5	4.80	2	15	121	143	3.24	<1	0.09	<10	1.36	2064	43	0.02	19	1263	9	0.09	<5	10	108	<5	0.10	<10	<10	97	<10	118	7
8V3190RA/RJ	HL08-37	120554	86.70	88.30	1.60	0.07	<0.1	1.29	14	41	<0.5	<5	3.25	3	15	99	91	2.73	<1	0.07	<10	1.09	1265	58	0.02	17	1417	14	0.04	<5	4	102	<5	0.09	<10	<10	64	<10	234	8
8V3190RA/RJ	HL08-37	120555	88.30	89.90	1.60	0.16	0.3	1.28	22	32	<0.5	<5	4.37	3	19	109	112	3.21	1	0.05	<10	0.93	1208	52	0.01	17	1280	26	0.08	<5	5	130	<5	0.09	<10	<10	78	<10	235	8
8V3190RA/RJ	HL08-37	120556	89.90	91.50	1.60	0.11	1.2	1.40	28	48	0.5	<5	4.47	3	20	168	212	3.39	<1	0.08	<10	1.18	1850	52	0.02	23	1417	27	0.23	<5	9	120	<5	0.09	<10	<10	114	<10	231	6
8V3190RA/RJ	HL08-37	120557	91.50	92.80	1.30	0.41	5.3	2.06	65	48	<0.5	<5	8.74	7	26	163	200	5.63	1	0.07	<10	1.58	3264	37	0.01	23	1241	1077	1.55	<5	12	184	<5	0.05	<10	13	126	<10	657	4
8V3190RA/RJ	HL08-37	120558	92.80	94.10	1.30	0.18	2.0	2.29	67	47	<0.5	<5	10.46	3	24	199	149	5.39	<1	0.05	<10	1.76	4034	51	0.01	27	1306	61	0.58	<5	15	195	<5	0.07	<10	15	156	<10	261	3
8V3190RA/RJ	HL08-37	120559	94.10	95.43	1.33	0.18	1.9	1.80	27	49	<0.5	<5	6.90	13	22	177	237	3.83	<1	0.08	<10	1.64	2458	39	0.01	24	1258	102	0.34	<5	10	142	<5	0.08	<10	<10	126	16	1210	3
8V3190RA/RJ	HL08-37	120560	95.43	97.15	1.72	0.10	1.1	2.17	18	46	<0.5	<5	5.47	3	25	193	156	4.28	<1	0.05	<10	2.46	1731	18	0.02	27	1282	45	0.20	<5	8	108	<5	0.12	<10	<10	132	<10	320	2
8V3190RA/RJ	HL08-37	120561	97.15	98.85	1.70	0.10	1.8	2.31	31	47	<0.5	<5	6.05	18	27	222	165	5.16	<1	0.07	<10	2.42	2748	19	0.01	31	1440	263	0.57	<5	17	153	<5	0.08	<10	<10	170	19	1697	2
8V3190RA/RJ	HL08-37	120562	98.85	100.58	1.73	0.06	2.5	2.00	31	66	<0.5	<5	7.79	7	26	223	160	5.05	<1	0.10	<10	2.31	2629	19	0.02	32	1371	359	0.49	<5	22	304	<5	0.04	<10	<10	171	<10	751	3
8V3190RA/RJ	HL08-37	120563	100.58	102.00	1.42	0.13	3.7	2.12	69	61	<0.5	<5	7.96	20	32	162	342	6.18	<1	0.07	<10	1.67	2885	26	0.01	28	1196	265	1.63	<5	10	187	<5	0.07	<10	12	131	22	1848	4
8V3190RA/RJ	HL08-37	120564	102.00	103.00	1.00	0.19	3.7	1.46	28	61	<0.5	<5	6.94	2	24	179	310	3.55	<1	0.09	<10	1.24	2179	33	0.02	28	1411	17	0.14	<5	13	166	<5	0.07	<10	<10	131	<10	179	5
8V3190RA/RJ	HL08-37	120565	103.00	104.00	1.00	0.18	3.3	1.73	37	51	<0.5	<5	8.10	14	25	191	255	4.26	<1	0.09	<10	1.47	2795	31	0.01	29	1320	163	0.65	<5	14	173	<5	0.06	<10	<10	145	15	1324	4
8V3190RA/RJ	HL08-37	120566	104.00	105.00	1.00	0.31	3.3	3.48	317	23	<0.5	<5	10.32	8	26	216	74	14.47	<1	0.02	<10	3.18	3426	39	<0.01	25	1275	212	>5.00	<5	17	64	<5	0.02	<10	28	183	<10	414	6
8V3190RA/RJ	HL08-37	120567	105.00	105.77	0.77	0.09	3.6	2.70	132	68	<0.5	<5	5.33	13	32	264	162	9.92	<1	0.08	<10	2.38	3037	13	0.01	30	1429	841	>5.00	<5	20	97	<5	0.04	<10	14	198	16	1151	4
8V3190RA/RJ	HL08-37	120568	105.77	106.51	0.74	<0.01	0.1	1.21	<5	187	<0.5	<5	2.41	<1	11	36	6	2.56	<1	0.24	10	0.78	560	<2	0.04	3	952	30	0.18	<5	3	55	<5	0.10	<10	<10	39	<10	81	5
8V3190RA/RJ	HL08-37	120569	109.50	110.75	1.25	0.13	3.2	1.76	30	88	<0.5	<5	10.24	2	29	252	335	4.99	<1	0.10	<10	1.14	2817	35	0.02	32	1388	49	0.36	<5	18	184	<5	0.10	<10	<10	182	<10	288	6
8V3190RA/RJ	HL08-37	120570	110.75	112.20	1.45	0.28	2.5	1.44	33	64	<0.5	<5	13.43	11	18	132	127	5.14	<1	0.07	<10	1.34	3405	56	0.01	19	942	134	0.75	<5	12	447	<5	0.03	<10	14	95	14	1082	3
8V3190RA/RJ	HL08-37	120571	112.20	113.70	1.50	0.25	3.8	2.04	52	44	<0.5	<5	8.00	7	26	200	428	5.66	<1	0.07	<10	1.75	2697	84	0.01	28	1246	190	1.34	<5	15	181	<5	<0.01	<10	<10	145	<10	624	2
8V3190RA/RJ	HL08-37	120572	113.70	115.20	1.50	0.13	4.0	2.47	108	66	<0.5	<5	5.00	55	23	215	188	9.39	<1	0.04	<10	2.21	2773	54	0.01	26	1166	496	>5.00	<5	17	95	<5	0.01	<10	15	163	55	5152	3
8V3190RA/RJ	HL08-37	120573	115.20	117.20	2.00	0.12	3.5	2.09	45	47	<0.5	<5	8.66	3	30	263	313	5.34	<1	0.09	<10	1.62	2870	41	0.01	34	1529	39	0.96	<5	21	171	<5	0.10	<10	<10	199	<10	291	3
8V3190RA/RJ	HL08-37	120574	117.20	118.30	1.10	0.10	3.8	2.18	50	39	<0.5	<5	9.71	59	26	233	232	6.54	<1	0.06	<10	1.65	2884	35	0.01	27	1259	252	2.52	<5	21	163	<5	0.08	<10	<10	178	61	5492	3
8V3190RA/RJ	HL08-37	120575	Std	PM1130	1.84	180.0	0.85	198	219	<0.5	<5	92	5.43	6	17	24	3705	3.64	4	0.17	<10	0.20	667	67	0.03	35	599	242	1.41	221	2	187	<5	0.06	<10	<10	22	19	265	9
8V3190RA/RJ	HL08-37	120576	118.30	120.00	1.70	0.17	2.8	1.34	51	32	<0.5	<5	>15.00	6	25	171	176	4.23	<1	0.09	<10	0.69	3266	36	<0.01	24	921	29	1.01	<5	16	216	<5	0.04	<10	10	126	<10	455	2
8V3190RA/RJ	HL08-37	120577	120.00	121.55	1.55	0.24	5.1	2.23	43	29	<0.5	<5	10.57	19	27	239	375	6.24	<1	0.04	<10	1.71	2707	47	0.01	30	1253	130	1.66	<5	21	198	<5	0.09	<10	<10	180	19	1727	3
8V3190RA/RJ	HL08-37	120578	121.55	123.00	1.45	0.33	11.4	1.97	178	35	<0.5	<5	6.95	194	28	177	928	9.58	<1	0.05	<10	1.51	2963	66	0.01	23	1031	1144	>5.00	<5	15	127	<5	0.02	<10	18	134	201	1890	4
8V3190RA/RJ	HL08-37	120579	123.00	123.90	0.90																																			

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																												
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm		
8V3190RA/RJ	HL08-37	120618	193.00	195.00	2.00	<0.01	1.7	1.84		41	48	<0.5	<5	9.32	1	25	172	108	4.10	<1	0.10	<10	1.57	1886	<2	<0.01	28	1122	24	0.51	<5	14	177	<5	0.01	<10	<10	107	<10	67	1	
8V3190RA/RJ	HL08-37	120619	195.00	197.00	2.00	0.01	1.0	1.99		42	43	<0.5	<5	8.90	1	24	160	49	4.20	<1	0.20	<10	1.62	1891	<2	<0.01	28	1153	17	0.48	<5	12	200	<5	0.02	<10	<10	94	<10	69	2	
8V3190RA/RJ	HL08-37	120620	197.00	199.00	2.00	0.04	1.2	2.01		36	64	<0.5	<5	8.29	1	24	167	64	4.72	<1	0.11	<10	1.55	2213	<2	<0.01	26	1106	27	0.74	<5	12	154	<5	0.01	<10	<10	104	<10	86	1	
8V3190RA/RJ	HL08-37	120621	199.00	200.45	1.45	0.30	3.0	1.48		98	85	<0.5	<5	3.39	9	18	63	131	3.66	<1	0.26	<10	0.88	1621	16	<0.01	9	1060	259	1.48	<5	5	81	<5	<0.01	<10	<10	56	<10	1087	1	
8V3190RA/RJ	HL08-37	120622	200.45	201.15	0.70	0.30	4.5	0.84		141	41	<0.5	<5	5.83	32	7	46	99	3.22	<1	0.10	<10	0.53	2358	5	<0.01	2	504	1767	1.80	<5	2	286	<5	<0.01	<10	<10	29	39	4143	1	
8V3190RA/RJ	HL08-37	120623	201.15	202.25	1.10	0.22	3.5	1.64		211	84	<0.5	<5	4.00	14	16	24	187	5.10	<1	0.17	<10	1.11	2372	13	<0.01	3	1125	257	1.78	<5	4	152	<5	0.01	<10	<10	78	14	1468	2	
8V3190RA/RJ	HL08-37	120624	202.25	203.50	1.25	0.40	4.3	0.84		346	50	<0.5	<5	8.00	46	8	31	155	4.28	<1	0.10	<10	0.60	2771	14	<0.01	2	537	592	3.48	<5	2	206	<5	<0.01	<10	<10	11	35	5377	1	
8V3190RA/RJ	HL08-37	120625	Std	PM1112		1.50	213.7	0.77		1849	103	<0.5	61	4.57	38	69	26	2325	3.11	1	0.08	<10	0.25	885	125	0.05	26	860	437	0.73	368	2	141	<5	0.03	<10	<10	20	19	368	6	
8V3190RA/RJ	HL08-37	120626	203.50	204.75	1.25	0.26	2.3	0.90		248	97	<0.5	<5	4.56	7	10	47	84	3.88	<1	0.16	<10	0.52	2238	15	<0.01	3	822	297	1.77	<5	3	92	<5	<0.01	<10	<10	45	<10	329	1	
8V3190RA/RJ	HL08-37	120627	204.75	206.00	1.25	0.24	3.0	1.19		135	131	<0.5	<5	3.55	14	12	52	157	4.62	<1	0.21	<10	0.65	2035	50	0.01	3	1071	286	1.69	<5	3	61	<5	<0.01	<10	<10	50	16	1870	1	
8V3190RA/RJ	HL08-37	120628	206.00	208.00	2.00	0.11	1.8	1.50		70	94	<0.5	<5	5.72	2	16	18	122	4.82	<1	0.19	<10	0.95	2291	9	0.01	3	1244	18	1.02	<5	3	156	<5	0.01	<10	<10	71	<10	217	1	
8V3215RA/RJ	HL08-37	120629	208.00	209.50	1.50	0.11	1.5	2.37		37	89	<0.5	<5	5.92	1	15	16	101	5.67	<1	0.24	<10	1.44	2592	7	0.01	2	1293	10	0.78	<5	4	225	<5	0.01	<10	<10	82	<10	156	2	
8V3215RA/RJ	HL08-37	120630	209.50	211.00	1.50	0.14	2.1	2.23		70	125	<0.5	<5	5.58	2	17	18	96	5.61	<1	0.38	<10	1.27	2695	8	0.01	3	1265	94	1.47	<5	3	140	<5	<0.01	<10	<10	65	<10	222	2	
8V3215RA/RJ	HL08-37	120631	211.00	213.00	2.00	0.14	1.3	1.73		81	140	<0.5	<5	8.82	3	14	31	44	4.19	<1	0.40	<10	0.82	2905	4	0.01	2	1191	43	1.20	<5	3	200	<5	<0.01	<10	<10	12	39	<10	166	1
8V3215RA/RJ	HL08-37	120632	213.00	215.00	2.00	0.10	2.6	1.83		85	144	<0.5	<5	7.20	2	14	18	122	4.81	<1	0.31	<10	0.98	2460	9	0.01	2	1102	29	1.21	<5	3	182	<5	<0.01	<10	<10	58	<10	144	1	
8V3215RA/RJ	HL08-37	120633	215.00	217.00	2.00	0.17	3.3	1.77		217	119	<0.5	<5	7.53	7	17	13	167	4.97	<1	0.28	<10	0.94	2857	9	0.01	2	1167	171	1.31	<5	4	152	<5	<0.01	<10	<10	13	69	<10	443	1
8V3215RA/RJ	HL08-37	120634	217.00	219.00	2.00	0.42	3.5	2.09		765	121	<0.5	<5	4.95	16	21	16	164	5.79	<1	0.26	<10	1.26	3102	8	0.01	3	1399	173	1.27	<5	6	125	<5	<0.01	<10	<10	13	110	<10	240	2
8V3215RA/RJ	HL08-37	120635	219.00	221.00	2.00	0.24	4.3	2.00		572	97	<0.5	<5	4.54	14	22	16	215	6.24	<1	0.23	<10	1.11	2755	11	0.01	3	1453	99	2.22	<5	5	113	<5	<0.01	<10	<10	102	<10	427	2	
8V3215RA/RJ	HL08-37	120636	221.00	222.00	1.00	0.53	8.3	2.06		380	122	<0.5	<5	3.11	67	25	26	332	6.22	<1	0.29	<10	1.23	2620	10	0.01	4	1550	1306	2.90	<5	5	83	<5	0.01	<10	<10	12	103	96	8462	2
8V3215RA/RJ	HL08-37	120637	222.00	223.00	1.00	0.29	7.4	1.63		430	113	<0.5	<5	5.64	59	18	26	303	5.57	<1	0.19	<10	0.94	2967	8	0.01	3	1216	1661	2.57	<5	5	158	<5	<0.01	<10	<10	13	91	58	5156	2
8V3215RA/RJ	HL08-37	120638	223.00	224.00	1.00	0.17	9.7	1.29		239	84	<0.5	<5	6.19	79	18	34	380	6.78	<1	0.28	<10	0.70	3266	6	0.01	2	1126	2694	>5.00	<5	3	159	<5	0.01	<10	<10	18	43	70	6335	2
8V3215RA/RJ	HL08-37	120639	224.00	225.00	1.00	0.10	2.4	0.71		175	135	<0.5	<5	4.71	4	12	44	11	3.53	<1	0.31	<10	0.29	2570	6	0.01	3	840	90	3.14	<5	1	141	<5	0.01	<10	<10	11	16	<10	156	1
8V3215RA/RJ	HL08-37	120640	225.00	227.00	2.00	0.12	2.2	1.21		160	120	<0.5	<5	2.94	4	13	36	73	4.32	<1	0.30	<10	0.70	2752	20	0.01	2	992	93	2.76	<5	2	83	<5	0.01	<10	<10	35	<10	254	1	
8V3215RA/RJ	HL08-37	120641	227.00	228.00	1.00	0.13	1.9	1.04		145	125	<0.5	<5	2.05	4	12	53	56	3.76	<1	0.28	<10	0.62	2331	7	0.01	2	921	132	2.56	<5	1	64	<5	0.02	<10	<10	29	<10	325	1	
8V3215RA/RJ	HL08-37	120642	228.00	230.00	2.00	0.25	2.5	0.83		182	111	<0.5	<5	7.38	5	11	41	29	3.40	<1	0.24	<10	0.46	2974	6	0.01	2	808	494	2.64	<5	2	164	<5	0.03	<10	<10	12	22	<10	274	1
8V3215RA/RJ	HL08-37	120643	230.00	232.00	2.00	0.20	3.0	2.08		213	80	<0.5	<5	5.38	6	18	22	90	5.92	<1	0.20	<10	1.40	3361	8	0.01	2	1189	226	2.19	<5	4	114	<5	0.09	<10	<10	16	80	<10	374	2
8V3215RA/RJ	HL08-37	120644	232.00	234.00	2.00	0.10	2.3	2.27		62	113	<0.5	<5	4.58	2	25	9	162	5.62	<1	0.30	<10	1.21	2340	7	0.02	2	1554	39	0.76	<5	6	125	<5	0.13	<10	<10	96	<10	175	2	
8V3215RA/RJ	HL08-37	120645	234.00	235.75	1.75	0.71	3.8	2.07		99	95	<0.5	<5	4.33	2	25	11	196	5.92	<1	0.28	<10	1.10	2323	7	0.02	2	1471	45	1.71	<5	5	117	<5	0.13	<10	<10	10	93	<10	170	2
8V3215RA/RJ	HL08-37	120646	235.75	236.59	0.84	0.11	3.0	2.19		37	149	<0.5	<5	4.64	2	25	9	188	5.27	<1	0.38	<10	1.06	2366	5	0.03	2	1588	15	0.89	<5	6	131	<5	0.14	<10	<10	93	<10	227	2	
HL08-38																																										

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																											
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm	
8V3190RA/RJ	HL08-38	120682	79.64	81.50	1.86	0.25	1.8	2.36	34	35	<0.5	<5	11.21	2	29	246	262	5.69	<1	0.08	<10	1.98	2895	28	0.01	31	1446	34	0.59	<5	19	191	<5	0.02	<10	<10	193	<10	260	2	
8V3190RA/RJ	HL08-38	120683	81.50	82.58	1.08	0.08	0.8	2.19	20	96	<0.5	<5	5.14	1	27	117	125	4.45	<1	0.07	<10	2.25	1450	13	0.02	20	1252	9	0.34	<5	9	146	<5	0.13	<10	<10	117	<10	141	6	
8V3190RA/RJ	HL08-38	120684	85.03	86.93	1.90	0.28	1.9	1.57	26	43	<0.5	<5	4.84	2	28	189	293	3.89	<1	0.07	<10	1.40	1420	41	0.02	27	1540	12	0.31	<5	6	122	<5	0.12	<10	<10	116	<10	237	3	
8V3215RA/RJ	HL08-38	120685	86.93	88.93	2.00	0.24	1.1	1.82	19	56	<0.5	<5	5.72	7	29	207	210	4.00	1	0.12	<10	1.59	1205	46	0.03	27	1501	18	0.30	<5	8	133	<5	0.15	<10	<10	132	<10	401	3	
8V3215RA/RJ	HL08-38	120686	88.93	90.89	1.96	0.20	0.6	1.73	12	65	<0.5	<5	3.18	3	25	163	187	3.64	<1	0.15	<10	1.70	752	49	0.04	23	1535	8	0.17	<5	5	112	<5	0.15	<10	<10	108	<10	236	2	
8V3215RA/RJ	HL08-38	120687	90.89	92.88	1.99	0.34	1.3	1.57	13	62	<0.5	<5	2.68	6	25	186	281	3.72	<1	0.11	<10	1.58	851	56	0.03	25	1526	147	0.24	<5	5	107	<5	0.15	<10	<10	109	<10	395	3	
8V3215RA/RJ	HL08-38	120688	92.88	94.86	1.98	0.34	1.3	1.63	17	48	<0.5	<5	4.60	4	28	196	317	3.91	<1	0.08	<10	1.55	1112	72	0.03	26	1520	44	0.34	<5	7	141	<5	0.14	<10	<10	117	<10	262	4	
8V3215RA/RJ	HL08-38	120689	94.86	96.78	1.92	0.48	1.0	1.20	13	42	<0.5	<5	3.17	1	24	160	308	2.93	<1	0.06	<10	1.13	711	76	0.02	23	1166	10	0.31	<5	5	100	<5	0.12	<10	<10	92	<10	107	2	
8V3215RA/RJ	HL08-38	120690	96.78	98.78	2.00	0.59	1.4	1.15	13	49	<0.5	<5	2.52	1	22	134	312	3.08	<1	0.06	<10	1.16	746	64	0.03	21	1144	11	0.39	<5	6	117	<5	0.10	<10	<10	92	<10	121	3	
8V3215RA/RJ	HL08-38	120691	98.78	100.65	1.87	0.33	1.6	1.09	16	48	<0.5	<5	2.98	6	20	131	240	2.87	<1	0.06	<10	1.07	880	44	0.03	19	1041	97	0.48	<5	5	146	<5	0.09	<10	<10	69	<10	361	3	
8V3215RA/RJ	HL08-38	120692	100.65	102.44	1.79	0.34	1.9	1.18	17	98	<0.5	<5	2.47	13	20	130	282	3.29	1	0.06	<10	1.01	747	31	0.03	19	1173	131	0.67	<5	4	114	<5	0.10	<10	<10	74	<10	706	3	
8V3215RA/RJ	HL08-38	120693	102.44	104.31	1.87	0.26	2.8	1.28	42	55	<0.5	<5	6.06	3	25	117	205	5.53	<1	0.09	<10	2.00	2383	51	0.01	23	1010	81	0.98	<5	17	279	<5	0.03	<10	11	91	<10	285	2	
8V3215RA/RJ	HL08-38	120694	104.31	106.22	1.91	0.65	3.0	1.53	27	99	<0.5	<5	4.93	2	27	178	340	4.64	<1	0.18	<10	1.44	1998	69	0.02	26	1077	14	0.34	<5	11	129	<5	0.10	<10	<10	131	<10	262	3	
8V3215RA/RJ	HL08-38	120695	106.22	108.09	1.87	0.52	2.3	1.71	45	37	<0.5	<5	5.93	3	25	184	269	4.79	<1	0.05	<10	1.51	2248	52	0.02	29	1085	91	0.32	<5	9	118	<5	0.10	<10	<10	137	<10	310	3	
8V3215RA/RJ	HL08-38	120696	108.09	110.09	2.00	0.53	1.6	1.70	22	45	<0.5	<5	3.31	2	29	198	280	4.94	<1	0.08	<10	1.65	1393	36	0.03	29	1108	10	0.12	<5	7	69	<5	0.13	<10	<10	139	<10	277	3	
8V3215RA/RJ	HL08-38	120697	110.09	112.09	2.00	0.81	2.1	1.39	20	49	<0.5	<5	2.79	3	27	182	340	4.09	1	0.07	<10	1.35	1208	84	0.03	26	1097	26	0.21	<5	7	84	<5	0.11	<10	<10	119	<10	317	2	
8V3215RA/RJ	HL08-38	120698	112.09	116.36	4.27	0.53	2.0	1.47	43	54	<0.5	<5	5.11	4	26	191	245	4.29	<1	0.09	<10	1.21	1891	97	0.02	26	1006	187	0.20	<5	10	100	<5	0.11	<10	<10	138	<10	308	2	
8V3215RA/RJ	HL08-38	120699	116.36	118.36	2.00	0.61	3.5	1.42	64	33	<0.5	<5	10.65	12	25	219	213	4.21	1	0.05	<10	0.75	3210	86	0.01	27	1009	73	0.48	<5	19	168	<5	0.06	<10	<10	160	<10	645	2	
8V3215RA/RJ	HL08-38	120700	Blank	Blank	Blank	Blank	<0.1	<0.1	8.89	<5	221	<0.5	<5	0.50	<1	8	101	4.11	1.82	<1	0.39	<10	0.55	576	<2	0.06	5	624	3	<0.01	<5	2	46	<5	0.11	<10	<10	35	<10	50	1
8V3215RA/RJ	HL08-38	120701	118.36	120.29	1.93	0.51	3.6	1.56	123	36	<0.5	<5	9.74	6	30	241	259	4.35	<1	0.07	<10	0.96	3055	87	<0.01	32	1194	27	0.65	<5	20	142	<5	0.06	<10	<10	179	<10	404	2	
8V3215RA/RJ	HL08-38	120702	120.29	122.29	2.00	0.76	3.0	2.30	35	40	<0.5	<5	8.23	4	35	271	293	5.86	<1	0.06	<10	1.54	2753	50	0.01	40	1240	12	0.32	<5	24	133	<5	0.10	<10	<10	212	<10	496	3	
8V3215RA/RJ	HL08-38	120703	122.29	123.78	1.49	0.49	3.4	2.31	43	40	<0.5	<5	9.75	6	32	274	297	5.39	1	0.06	<10	1.79	3159	24	0.01	33	1327	120	0.31	<5	25	177	<5	0.07	<10	<10	208	11	574	2	
8V3215RA/RJ	HL08-38	120704	123.78	125.27	1.49	0.14	2.7	1.82	333	37	<0.5	<5	9.47	12	34	224	209	4.67	1	0.05	<10	1.39	3674	17	<0.01	30	1082	43	0.77	<5	18	198	<5	0.01	<10	<10	169	<10	540	1	
8V3215RA/RJ	HL08-38	120705	125.27	126.65	1.38	0.10	2.4	2.09	79	36	<0.5	<5	8.85	4	34	278	205	5.18	<1	0.05	<10	1.44	3024	37	0.01	34	1345	10	0.51	<5	24	158	<5	0.08	<10	<10	203	<10	269	2	
8V3215RA/RJ	HL08-38	120706	126.65	128.32	1.67	0.18	2.9	2.05	88	71	<0.5	<5	9.09	4	36	251	288	5.47	1	0.11	<10	1.32	3331	18	0.02	40	1242	120	0.74	<5	23	194	<5	0.03	<10	<10	195	<10	242	2	
8V3215RA/RJ	HL08-38	120707	128.32	129.37	1.05	0.02	<0.1	0.98	<5	190	<0.5	<5	2.68	<1	7	34	6	1.84	<1	0.26	<10	0.56	587	<2	0.03	3	750	36	0.10	<5	2	159	<5	<0.01	<10	<10	15	<10	56	3	
8V3215RA/RJ	HL08-38	120708	133.07	135.25	2.18	0.31	3.1	1.87	271	56	<0.5	<5	9.02	8	28	220	280	4.68	1	0.10	<10	1.46	3034	27	0.02	29	1263	89	0.70	<5	17	139	<5	0.10	<10	<10	165	<10	344	2	
8V3215RA/RJ	HL08-38	120709	135.25	137.37	2.12	0.45	3.2	1.63	742	60	<0.5	<5	5.19	21	29	216	228	4.41	1	0.10	<10	1.40	2013	35	0.02	30	1301	126	1.11	8	111	112	<5	0.08	<10	<10	137	<10	624	2	
8V3215RA/RJ	HL08-38	120710	137.37	139.31	1.94	0.21	1.8	2.17	60	156	<0.5	<5	6.02	2	33	239	187	5.35	<1	0.42	<10	1.56	2379	31	0.07	35	1333	38	0.62	<5	17	136	<5	0.09	<10	<10	167	<10	184	3	
8V3215RA/RJ	HL08-38	120711	148.05	150.05	2.00	0.03	0.3	1.36	7	605	<0.5	<5	3.37	<1	20	192	30	3.28	1	0.10	<10	1.13	1297	21	0.03	26	1363	5	0.12	<5											

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																												
					0.5-1.0	1.0-3.0	3.0-5.0	>5.0	5-10	10-50	50-100	>100	2500-5000	5000-10000	>10000	S	Sb	Sc	Sr	Th	Ti	U	V	W	Zn	Zr															
8V3215RA/RJ	HL08-38	125754	224.90	226.58	1.68	0.13	3.8	1.42	128	102	<0.5	<5	5.17	5	13	16	177	4.34	<1	0.31	<10	0.64	2391	34	0.01	2	1072	178	1.41	<5	3	213	<5	0.01	<10	13	45	<10	316	1	
8V3215RA/RJ	HL08-38	125755	226.58	228.58	2.00	0.05	1.9	2.25	25	105	<0.5	<5	2.96	1	23	9	113	5.68	<1	0.31	<10	0.94	1881	8	0.01	4	1127	21	0.99	<5	4	103	<5	0.06	<10	<10	81	<10	153	2	
8V3215RA/RJ	HL08-38	125756	228.58	230.58	2.00	0.29	2.1	2.19	22	94	<0.5	<5	4.91	4	19	9	178	4.81	<1	0.25	<10	1.27	1948	8	0.02	3	1047	171	0.46	<5	4	180	<5	0.04	<10	<10	75	<10	466	2	
8V3215RA/RJ	HL08-38	125757	230.58	232.58	2.00	0.26	23.9	2.06	29	97	<0.5	<5	3.53	49	20	8	929	5.11	<1	0.25	<10	1.13	1965	12	0.01	3	1052	9473	1.36	9	4	119	<5	0.01	<10	<10	80	48	4991	1	
8V3215RA/RJ	HL08-38	125758	232.58	234.44	1.86	0.32	2.9	2.46	10	77	<0.5	<5	4.90	18	19	9	250	5.16	<1	0.13	<10	1.76	2027	20	0.02	3	990	136	0.51	<5	6	175	<5	0.06	<10	<10	92	17	1684	2	
8V3215RA/RJ	HL08-38	125759	234.44	235.88	1.44	0.67	1.7	2.41	<5	95	<0.5	<5	4.48	3	21	7	213	5.06	<1	0.21	<10	1.38	1698	5	0.02	3	1042	45	0.29	<5	5	169	<5	0.06	<10	<10	74	<10	337	3	
8V3215RA/RJ	HL08-38	125760	235.88	237.88	2.00	0.45	2.0	2.13	15	136	<0.5	<5	3.58	3	20	8	176	5.16	<1	0.30	<10	1.04	1757	2	0.02	3	1140	27	0.76	<5	4	119	<5	0.06	<10	<10	65	<10	344	2	
8V3215RA/RJ	HL08-38	125761	237.88	239.88	2.00	0.09	0.6	2.00	<5	90	<0.5	<5	4.41	<1	19	5	58	4.35	<1	0.26	<10	1.16	1586	2	0.02	2	1092	19	0.59	<5	4	133	<5	0.07	<10	<10	63	<10	119	2	
8V3215RA/RJ	HL08-38	125762	239.88	241.88	2.00	0.03	0.9	2.10	11	92	<0.5	<5	4.44	2	22	5	75	5.03	<1	0.27	<10	1.11	1826	7	0.02	3	1126	49	0.75	<5	4	142	<5	0.06	<10	<10	59	<10	202	2	
8V3215RA/RJ	HL08-38	125763	241.88	243.85	1.97	0.06	1.1	2.13	28	95	<0.5	<5	6.45	1	21	4	77	4.94	<1	0.27	<10	1.11	2330	4	0.01	2	1065	28	0.57	<5	3	319	<5	0.06	<10	<10	58	<10	128	2	
8V3215RA/RJ	HL08-38	125764	243.85	245.85	2.00	0.33	2.2	2.09	94	105	<0.5	<5	3.60	12	20	10	90	5.52	<1	0.21	<10	1.11	2581	7	0.01	3	1047	257	1.24	<5	4	183	<5	0.04	<10	<10	12	78	12	1232	2
8V3215RA/RJ	HL08-38	125765	245.85	247.85	2.00	0.26	2.5	1.89	41	110	<0.5	<5	3.88	6	19	7	192	4.80	<1	0.31	<10	0.90	2045	2	0.02	2	1072	37	1.01	<5	3	132	<5	0.02	<10	<10	51	<10	593	2	
8V3215RA/RJ	HL08-38	125766	247.85	249.85	2.00	0.43	2.8	2.27	49	101	<0.5	<5	2.79	5	22	11	182	5.79	<1	0.27	<10	1.13	2130	4	0.01	3	1043	605	0.94	<5	4	91	<5	0.01	<10	<10	71	<10	419	2	
8V3215RA/RJ	HL08-38	125767	249.85	251.83	1.98	0.23	1.0	2.02	8	124	<0.5	<5	3.27	2	19	6	76	4.77	<1	0.30	<10	0.92	1957	21	0.01	2	1108	39	0.46	<5	3	146	<5	<0.01	<10	<10	54	<10	205	1	
8V3215RA/RJ	HL08-38	125768	251.83	253.83	2.00	0.05	1.1	2.07	19	105	<0.5	<5	3.51	1	19	8	67	5.06	<1	0.27	<10	0.97	2102	6	0.01	2	1098	43	0.74	<5	3	135	<5	<0.01	<10	<10	59	<10	132	1	
8V3215RA/RJ	HL08-38	125769	253.83	255.83	2.00	0.07	7.0	2.08	78	95	<0.5	<5	2.59	27	19	8	348	5.84	<1	0.25	<10	1.08	1869	<2	0.01	2	988	126	1.84	<5	3	88	<5	<0.01	<10	<10	13	60	24	2507	2
8V3215RA/RJ	HL08-38	125770	255.83	257.83	2.00	0.13	1.7	2.09	87	89	<0.5	<5	2.20	5	20	8	68	5.86	<1	0.23	<10	1.05	1700	<2	0.01	3	1033	62	1.67	<5	3	88	<5	<0.01	<10	<10	61	<10	411	2	
8V3215RA/RJ	HL08-38	125771	257.83	259.83	2.00	0.02	1.0	2.03	38	96	<0.5	<5	3.29	1	17	7	47	4.99	<1	0.27	<10	0.96	1999	<2	0.01	2	1079	24	0.74	<5	3	121	<5	<0.01	<10	<10	60	<10	116	2	
8V3215RA/RJ	HL08-38	125772	259.83	261.83	2.00	0.04	0.9	1.70	33	91	<0.5	<5	4.93	6	14	12	35	3.86	<1	0.28	<10	0.93	1601	<2	0.01	2	966	35	0.72	<5	2	170	<5	<0.01	<10	<10	35	<10	467	1	
8V3215RA/RJ	HL08-38	125773	261.83	264.02	2.19	0.03	0.6	1.88	15	96	<0.5	<5	4.93	<1	17	5	34	3.93	<1	0.27	10	1.15	1546	<2	0.01	2	1055	36	0.48	<5	2	139	<5	0.02	<10	<10	47	<10	66	1	
HL08-39 - Zone: Sparky, Pad 29: 435302E,6222460N, Elev: 1204m, Az :357, Dip: -46, EOH: 132.93m																																									
8V3215RA/RJ	HL08-39	125774	2.27	3.00	0.73	0.01	<0.1	0.21	<5	34	<0.5	<5	0.20	<1	1	80	1	0.51	<1	0.19	13	0.01	234	<2	0.04	2	24	25	0.01	<5	<1	6	15	<0.01	<10	<10	1	<10	29	6	
8V3215RA/RJ	HL08-39	125775	Std	PM 9.2	5.93	3.0	1.41	568	190	<0.5	<5	8.15	13	50	75	450	5.62	<1	0.16	12	0.35	825	107	0.04	73	807	87	2.40	<5	3	120	<5	0.09	<10	<10	39	36	98	12		
8V3215RA/RJ	HL08-39	125776	4.92	6.65	1.73	0.02	1.2	1.95	31	110	<0.5	<5	2.93	<1	26	7	53	4.40	<1	0.27	<10	0.99	1531	<2	0.02	3	1401	15	0.65	<5	5	81	<5	<0.01	<10	<10	77	<10	92	1	
8V3215RA/RJ	HL08-39	125777	6.65	7.20	0.55	<0.1	<0.1	1.14	6	1432	<0.5	<5	2.85	<1	10	51	5	3.49	<1	0.22	32	0.97	864	2	0.04	8	1574	16	0.13	<5	4	102	<5	0.01	<10	<10	44	<10	73	4	
8V3215RA/RJ	HL08-39	125778	9.40	11.00	1.60	3.00	1.8	2.29	47	97	<0.5	<5	4.47	1	22	5	53	6.09	<1	0.30	<10	1.18	2094	<2	0.03	2	1514	33	1.06	<5	6	132	<5	<0.01	<10	<10	103	<10	142	2	
8V3215RA/RJ	HL08-39	125779	11.00	12.25	1.25	1.20	1.6	2.33	79	77	<0.5	<5	5.13	3	22	15	36	6.13	<1	0.25	<10	1.58	2644	<2	0.01	3	1334	30	1.40	<5	4	160	<5	<0.01	<10	<10	14	80	<10	263	2
8V3215RA/RJ	HL08-39	125780	12.25	13.40	1.15	0.09	4.0	1.78	110	109	<0.5	<5	6.88	7	20	10	84	5.56	<1	0.27	<10	0.87	2715	<2	0.01	2	1166	119	1.39	<5	5	323	<5	0.01	<10	<10	16	72	<10	565	2
8V3215RA/RJ	HL08-39	125781	13.40	14.35	0.95	0.15	3.0	2.03	46	61	<0.5	<5	8.57	1	18	26	82	6.11	<1	0.18	<10	0.85	3851	<2	0.02	2	964	26	0.90	<5	5	150	<5	0.04	<10	<10	21	79	<10	97	3
8V3215RA/RJ	HL08-39	125782	14.35	15.00	0.65	0.01	<0.1	0.96	<5	526	<0.5	<5	3.05	<1	8	35	<1	2.12	<1	0.21	12	0.73	497	<2	0.03	4	764	4	0.04	<5	2	94	<5	<0.01	<10	<10	23	<10	45	4	
8V3215RA/RJ	HL08-39	125783	22.98	24.70	1.72	0.58	3.4	1.66	113	168	<0.5	<5	6.40	3	20	17	74	4.90	<1	0.35	<10	0.81	2259	<2	0.01	3	1154	63	1.56	<5	5	191	<5	0.01	<10	<10	61				

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																												
						0.5-1.0	1.0-3.0	3.0-5.0	>5.0	5-10	10-50	50-100	>100	2500-5000	5000-10000	>10000	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Zr														
8V3215RA/RJ	HLO8-39	125825	Std	PM 1116		0.11	765.3	0.65	487	187	<0.5	136	0.58	21	7	20	7506	2.44	5	0.16	<0.62	294	459	0.03	4	346	949	1.28	1422	2	75	<5	0.05	<10	<10	22	<10	938	2			
8V3215RA/RJ	HLO8-39	125826	107.50	109.50	2.00	0.31	6.4	1.10	1100	108	<0.5	<5	0.90	34	17	45	74	5.08	<1	0.36	<10	0.49	966	4	<0.01	5	814	114	3.19	21	2	36	<5	<0.01	<10	<10	30	<10	626	2		
8V3215RA/RJ	HLO8-39	125827	109.50	111.15	1.65	0.15	5.4	1.08	466	118	<0.5	<5	0.93	12	20	28	105	4.43	<1	0.43	<10	0.41	815	<2	<0.01	4	1256	30	2.79	11	3	39	<5	<0.01	<10	<10	40	<10	58	2		
8V3215RA/RJ	HLO8-39	125828	111.15	112.80	1.65	0.14	3.1	1.36	182	120	<0.5	<5	3.23	5	17	23	51	4.53	<1	0.37	<10	0.66	1207	<2	<0.01	6	663	28	2.07	<5	2	78	<5	<0.01	<10	<10	47	<10	77	2		
8V3215RA/RJ	HLO8-39	125829	112.80	114.26	1.46	0.02	2.0	1.92	40	126	<0.5	<5	6.93	1	19	16	58	4.27	<1	0.34	<10	1.18	1957	<2	<0.01	7	1097	19	0.59	<5	4	161	<5	<0.01	<10	<10	75	<10	49	1		
8V3215RA/RJ	HLO8-39	125830	114.26	115.65	1.39	0.09	2.5	1.25	98	125	<0.5	<5	2.95	3	12	21	48	3.52	<1	0.34	<10	0.51	1552	2	<0.01	4	970	73	1.02	<5	2	110	<5	<0.01	<10	<10	37	<10	82	1		
8V3215RA/RJ	HLO8-39	125831	115.65	117.00	1.35	0.06	3.4	1.51	88	148	<0.5	<5	1.58	3	15	19	59	4.07	<1	0.40	<10	0.61	1362	3	<0.01	5	1071	43	1.14	<5	3	67	<5	<0.01	<10	<10	48	<10	146	2		
8V3215RA/RJ	HLO8-39	125832	117.00	119.00	2.00	0.18	8.1	1.26	468	117	<0.5	<5	2.45	13	18	42	85	4.80	<1	0.41	<10	0.49	1261	2	<0.01	5	907	79	2.73	6	3	79	<5	<0.01	<10	<10	41	<10	182	2		
8V3215RA/RJ	HLO8-39	125833	119.00	120.00	1.00	0.20	8.8	1.02	556	61	<0.5	<5	0.69	16	24	36	217	6.48	<1	0.46	<10	0.34	545	<2	<0.01	4	1197	71	>5.00	9	3	31	<5	<0.01	<10	<10	27	<10	210	3		
8V3283RA/RJ	HLO8-39	125834	120.00	121.40	1.40	0.47	5.3	0.77	843	44	<0.5	<5	0.79	18	15	41	22	8.11	<1	0.40	<10	0.22	538	<2	0.01	4	1027	51	>5.00	<5	3	38	<5	<0.01	<10	12	22	<10	82	4		
8V3283RA/RJ	HLO8-39	125835	121.40	123.49	2.09	5.32	8.1	0.41	>10000	86	<0.5	<5	2.09	265	15	58	46	3.87	<1	0.32	<10	0.05	641	7	0.01	4	870	71	3.41	186	1	84	<5	<0.01	<10	10	14	<10	103	2		
8V3283RA/RJ	HLO8-39	125836	123.49	125.55	2.06	1.39	5.0	1.23	450	87	<0.5	<5	0.82	10	25	23	76	5.06	<1	0.37	<10	0.48	1074	2	0.01	4	1550	39	3.21	<5	3	41	<5	<0.01	<10	<10	47	<10	99	2		
8V3283RA/RJ	HLO8-39	125837	125.55	127.61	2.06	0.25	4.1	1.19	359	88	<0.5	<5	2.01	8	21	34	55	5.14	<1	0.35	<10	0.42	1269	3	0.01	3	1426	51	3.27	<5	3	72	<5	<0.01	<10	<10	50	<10	111	2		
8V3283RA/RJ	HLO8-39	125838	127.61	129.62	2.01	0.12	1.5	1.92	152	158	<0.5	<5	4.35	3	18	17	37	4.88	<1	0.32	<10	1.16	2231	<2	0.02	3	1802	36	1.47	<5	4	232	<5	<0.01	<10	<10	71	<10	114	2		
8V3283RA/RJ	HLO8-39	125839	129.62	130.33	0.71	0.07	2.4	0.26	128	32	<0.5	<5	10.74	3	6	81	37	1.52	<1	0.16	<10	0.10	5462	<2	0.01	3	443	47	1.38	<5	1	276	<5	<0.01	<10	29	8	<10	71	<10	<10	3
8V3283RA/RJ	HLO8-39	125840	130.33	131.60	1.27	0.04	0.8	2.13	58	85	<0.5	<5	4.02	1	21	50	26	4.92	<1	0.24	19	1.56	1308	<2	0.02	13	2599	15	0.58	<5	4	172	<5	0.01	<10	<10	72	<10	122	3		
8V3283RA/RJ	HLO8-39	125841	131.60	132.93	1.33	0.03	2.7	1.99	362	83	<0.5	<5	3.56	8	23	17	52	5.80	<1	0.31	<10	1.27	1929	<2	0.01	4	1860	46	2.19	<5	4	118	<5	0.02	<10	<11	95	<10	155	2		
HLO8-40 - Zone: Sparky, Pad 29: 435302E,6222460N, Elev: 1204m, Az: 357, Dip: -66, EOH: 151.52m																																										
8V3283RA/RJ	HLO8-40	125842	5.42	7.42	2.00	0.04	1.1	1.98	66	343	<0.5	<5	3.47	1	22	11	37	5.31	<1	0.36	12	0.99	1606	<2	0.02	3	1920	16	1.08	<5	5	114	<5	0.01	<10	<10	79	<10	92	3		
8V3283RA/RJ	HLO8-40	125843	7.42	9.02	1.60	<0.01	<0.1	1.20	12	1643	<0.5	<5	2.76	<1	10	56	<1	3.36	<1	0.26	44	0.93	837	<2	0.03	8	2103	11	0.08	<5	3	98	<5	0.01	<10	<10	48	<10	73	5		
8V3283RA/RJ	HLO8-40	125844	9.02	10.58	1.56	0.01	1.5	1.94	161	202	<0.5	<5	3.23	5	19	19	52	5.05	<1	0.42	16	1.04	1396	<2	0.02	4	1908	52	1.48	<5	5	96	<5	0.01	<10	<10	73	<10	205	4		
8V3283RA/RJ	HLO8-40	125845	10.58	12.07	1.49	0.02	1.8	2.22	62	112	<0.5	<5	3.58	3	23	12	66	6.06	<1	0.29	<10	1.22	2023	<2	0.02	3	1773	18	1.45	<5	4	120	<5	0.01	<10	13	81	<10	228	2		
8V3283RA/RJ	HLO8-40	125846	12.07	13.82	1.75	0.02	2.1	2.10	79	97	<0.5	<5	4.66	2	20	9	38	5.49	<1	0.32	<10	1.10	2457	<2	0.02	2	1722	13	1.09	<5	5	151	<5	<0.01	<10	13	75	<10	146	2		
8V3283RA/RJ	HLO8-40	125847	13.82	15.16	1.34	0.08	6.0	2.26	108	153	<0.5	<5	5.13	2	21	15	47	5.49	<1	0.46	<10	1.06	2428	<2	0.03	2	1751	37	1.43	<5	6	155	<5	0.02	<10	13	92	<10	124	2		
8V3283RA/RJ	HLO8-40	125848	15.16	16.48	1.32	1.09	3.1	1.03	572	89	<0.5	<5	2.74	13	16	41	41	4.23	<1	0.33	<10	0.36	1079	7	0.01	3	1409	26	2.50	<5	3	98	<5	<0.01	<10	<10	34	<10	76	2		
8V3283RA/RJ	HLO8-40	125849	16.48	17.38	0.90	0.02	<0.1	1.02	18	338	<0.5	<5	2.65	<1	9	37	5	2.19	<1	0.23	13	0.70	474	<2	0.04	5	1093	8	0.25	<5	2	101	<5	<0.01	<10	<10	31	<10	44	5		
8V3283RA/RJ	HLO8-40	125850	Blank	Blank		0.01	<0.1	0.90	<5	242	<0.5	<5	0.44	<1	8	106	<1	2.04	<1	0.47	<10	0.62	566	<2	0.05	5	865	<2	<0.01	<5	2	41	<5	0.14	<10	<10	39	<10	51	2		
8V3283RA/RJ	HLO8-40	125851	25.23	26.77	1.54	0.15	2.8	2.14	111	127	<0.5	<5	3.45	3	24	17	71	6.22	<1	0.35	<10	1.03	2627	<2	0.01	3	1786	152	1.69	<5	5	127	<5	<0.01	<10	16	85	<10	201	2		
8V3283RA/RJ	HLO8-40	125852	26.77	28.73	1.96	0.24	3.1	1.76	176	72	<0.5	<5	3.59	5	23	19	55	5.49	<1	0.30	<10	0.82	2324	<2	0.01	3	1845	93	1.76	<5	4	139	<5	<0.01	<10	13	71	<10	235	2		
8V3283RA/RJ	HLO8-40	125853	28.73	30.58	1.85	0.24	3.8	1.48	368	82	<0.5	<5	3.81	10	22	17	49	5.65	<1	0.34	<10	0.67	2294	<2	0.01	3	1814	127	2.87	<5	4	143	<5	<0.01	<10	14	60	<10	396	2		
8V3283RA/RJ	HLO8-40	125854	30.58	31.38	0.80	0.25	3.3	1.38	324	88	<0.5	<5	3.09	8	26	16	57	5.86	<1	0.34	<10	0.76	2291	<2	0.01	3	2030	76	2.06	<5	4	147	<5	<0.01	<10	16	62					

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn: 2500-5000										5000-10000				>10000													
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3283RA/RJ	HL08-40	125896	112.43	114.12	1.69	0.08	2.5	1.29	145	98	<0.5	<5	1.12	4	13	8	24	4.30	<1	0.28	<10	0.73	1113	<2	0.01	1	1173	69	2.06	<5	2	59	<5	<0.01	<10	<10	40	<10	154	2
8V3283RA/RJ	HL08-40	125897	114.12	115.53	1.41	0.15	2.7	0.99	373	102	<0.5	<5	1.33	9	17	16	22	4.10	<1	0.34	<10	0.50	926	<2	0.01	3	1135	50	3.05	<5	2	67	<5	<0.01	<10	<10	29	<10	95	2
8V3215RA/RJ	HL08-40	125898	115.53	116.88	1.35	0.22	6.5	0.37	269	84	<0.5	<5	7.78	11	9	70	28	2.91	<1	0.23	<10	0.16	2076	4	<0.01	3	512	189	2.78	6	1	290	<5	<0.01	<10	11	<10	597	1	
8V3283RA/RJ	HL08-40	125899	116.88	119.14	2.26	0.07	1.8	1.24	77	115	<0.5	<5	2.41	3	14	9	33	4.00	<1	0.29	<10	0.69	1551	<2	0.01	1	1175	74	1.59	<5	3	138	<5	<0.01	<10	<10	39	<10	259	2
8V3283RA/RJ	HL08-40	125900	Blank	Blank	<0.01	<0.1	0.93	<5	264	<0.5	<5	0.50	<1	9	85	1	2.09	<1	0.47	<10	0.60	613	<2	0.05	6	699	4	0.01	<5	2	44	<5	0.12	<10	<10	41	<10	52	2	
8V3283RA/RJ	HL08-40	125901	119.14	121.14	2.00	0.03	1.3	1.54	32	97	<0.5	<5	1.88	1	15	5	31	4.47	<1	0.30	<10	0.91	1365	2	0.01	1	1197	30	1.48	<5	3	121	<5	<0.01	<10	<10	46	<10	75	2
8V3283RA/RJ	HL08-40	125902	121.14	123.16	2.02	0.24	2.6	1.62	123	68	<0.5	<5	4.64	4	19	12	58	4.53	<1	0.24	<10	1.10	2125	2	0.01	4	1087	66	1.67	<5	3	241	<5	<0.01	<10	14	54	<10	139	1
8V3283RA/RJ	HL08-40	125903	123.16	124.97	1.81	0.11	2.5	1.76	156	66	<0.5	<5	3.56	5	21	8	52	4.87	<1	0.26	<10	1.23	2296	2	0.01	5	1174	82	1.59	<5	4	170	<5	<0.01	<10	13	63	<10	204	2
8V3283RA/RJ	HL08-40	125904	124.97	126.83	1.86	0.19	2.8	2.51	95	66	<0.5	<5	4.15	3	32	12	70	6.55	<1	0.31	<10	1.57	2574	7	0.01	10	1171	63	1.80	<5	5	192	<5	<0.01	<10	17	89	<10	204	2
8V3283RA/RJ	HL08-40	125905	126.83	128.40	1.57	0.06	2.9	0.56	117	56	<0.5	<5	6.69	4	11	34	19	2.92	<1	0.23	<10	0.34	3308	<2	0.01	2	637	241	2.04	<5	2	339	<5	<0.01	<10	15	15	<10	148	<1
8V3283RA/RJ	HL08-40	125906	128.40	130.01	1.61	0.02	1.2	2.02	69	84	<0.5	<5	5.64	2	19	6	28	5.04	<1	0.30	<10	1.01	2676	<2	0.01	2	1439	38	1.17	<5	4	224	<5	<0.01	<10	16	61	<10	126	1
8V3283RA/RJ	HL08-40	125907	130.01	131.69	1.68	0.07	0.8	1.39	549	127	0.9	<5	7.70	14	13	12	36	2.92	<1	0.39	<10	0.54	2322	<2	0.01	2	1244	29	0.55	<5	3	212	<5	<0.01	<10	<10	33	<10	156	1
8V3283RA/RJ	HL08-40	125908	135.26	137.26	2.00	0.13	1.3	1.68	1426	148	<0.5	<5	7.77	36	14	19	14	3.41	<1	0.34	12	0.80	3486	9	0.03	4	1295	41	0.51	7	3	173	<5	0.09	<10	14	45	<10	200	3
8V3283RA/RJ	HL08-40	125909	137.26	139.26	2.00	0.01	0.7	1.98	330	113	<0.5	<5	4.90	8	17	23	18	4.20	<1	0.29	12	1.21	2180	<2	0.05	6	1495	31	0.48	<5	4	126	<5	0.15	<10	<10	54	<10	137	7
8V3283RA/RJ	HL08-40	125910	139.26	141.01	1.75	0.02	0.9	1.63	59	133	<0.5	<5	3.34	2	14	5	27	3.93	<1	0.38	<10	0.65	1914	<2	0.03	2	1361	45	1.14	<5	2	101	<5	0.07	<10	<10	37	<10	137	1
8V3283RA/RJ	HL08-40	125911	141.01	142.51	1.50	0.01	1.1	2.84	40	176	<0.5	<5	4.20	3	21	8	43	5.23	<1	0.49	<10	1.18	2412	<2	0.11	2	1348	37	1.45	<5	4	121	<5	0.09	<10	13	61	<10	336	2
8V3283RA/RJ	HL08-40	125912	146.82	148.48	1.66	0.01	0.6	2.01	16	91	<0.5	<5	10.00	1	16	20	25	3.51	<1	0.30	<10	1.05	2681	<2	0.05	5	1225	21	0.43	<5	4	201	<5	0.11	<10	11	62	<10	106	3
8V3283RA/RJ	HL08-40	125913	148.48	150.57	2.09	0.03	0.9	3.09	39	93	<0.5	<5	14.96	2	12	8	31	4.29	<1	0.27	<10	1.20	3551	<2	0.09	1	820	29	0.66	<5	4	365	<5	0.09	<10	18	69	<10	146	3
HL08-41 - Zone: Sparky, Pad 29: 435302E, 6222460N, Elev: 1204m, Az: 026, Dip: -45, EOH: 127.13m																																								
8V3215RA/RJ	HL08-41	125914	1.95	2.50	0.55	0.02	0.2	0.31	5	41	<0.5	<5	0.45	<1	1	119	3	0.63	<1	0.26	13	0.01	364	<2	0.07	2	31	21	0.05	<5	1	10	13	<0.01	<10	<10	1	<10	18	7
8V3215RA/RJ	HL08-41	125915	6.70	7.20	0.50	0.04	1.3	1.68	88	283	0.7	<5	2.16	2	27	31	38	5.77	<1	0.37	12	0.88	1207	2	0.02	5	1316	25	1.29	<5	4	67	<5	<0.01	<10	<10	59	<10	116	4
8V3215RA/RJ	HL08-41	125916	9.11	11.10	1.99	0.03	1.6	2.22	53	266	0.5	<5	4.89	1	18	16	51	5.84	<1	0.32	<10	1.15	1933	<2	0.02	2	1388	21	1.28	<5	5	181	<5	<0.01	<10	11	86	<10	92	2
8V3283RA/RJ	HL08-41	125917	11.10	13.12	2.02	0.03	1.8	2.11	54	84	<0.5	<5	4.59	1	21	5	57	5.50	<1	0.24	<10	1.12	2270	<2	0.02	2	1450	21	1.07	<5	5	184	<5	<0.01	<10	12	92	<10	110	2
8V3283RA/RJ	HL08-41	125918	13.12	15.12	2.00	0.11	2.4	2.05	82	111	<0.5	<5	4.47	2	25	4	63	5.70	<1	0.39	<10	0.92	2243	<2	0.01	3	1543	32	1.66	<5	5	167	<5	0.01	<10	13	67	<10	112	2
8V3283RA/RJ	HL08-41	125919	15.12	17.13	2.01	0.26	2.0	3.34	53	132	<0.5	<5	3.91	1	35	12	87	6.60	<1	0.36	<10	1.27	2351	<2	0.16	4	1818	39	1.65	<5	9	98	<5	0.09	<10	<10	156	<10	143	4
8V3283RA/RJ	HL08-41	125920	17.13	17.70	0.57	0.02	<0.1	1.06	<5	778	<0.5	<5	3.20	<1	9	19	<1	2.26	<1	0.22	16	0.75	561	<2	0.03	5	872	3	0.03	<5	2	111	<5	<0.01	<10	<10	27	<10	50	4
8V3283RA/RJ	HL08-41	125921	28.16	30.00	1.84	0.03	1.3	2.38	29	245	<0.5	<5	5.58	1	25	5	67	6.11	<1	0.35	11	1.10	2426	<2	0.04	3	1794	57	0.89	<5	8	301	<5	0.01	<10	13	107	<10	199	2
8V3283RA/RJ	HL08-41	125922	30.00	32.00	2.00	0.04	1.2	1.85	43	130	<0.5	<5	5.21	1	24	6	73	5.31	<1	0.31	<10	0.94	2262	<2	0.02	2	1670	27	0.88	<5	6	343	<5	<0.01	<10	12	82	<10	167	2
8V3283RA/RJ	HL08-41	125923	32.00	34.00	2.00	0.06	2.2	2.06	34	190	<0.5	<5	4.73	2	27	4	70	5.70	<1	0.36	<10	0.96	2516	<2	0.01	3	1735	54	1.29	<5	5	241	<5	<0.01	<10	14	78	<10	253	2
8V3283RA/RJ	HL08-41	125924	34.00	36.00	2.00	0.55	2.8	1.91	64	131	<0.5	<5	5.54	2	21	6	63	5.24	<1	0.34	<10	0.84	2586	<2	0.01	2	1566	35	1.14	<5	5	263	<5	<0.01	<10	14	70	<10	174	2
8V3283RA/RJ	HL08-41	125925	Std	PM 197	0.43	0.6	1.13	6146	25	<0.5	<5	16	6.55	152	199	13	79	4.09	<1	0.05	13	0.26	817	13	0.09	36	12595	14	1.57	<5	2	104								

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:				S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Zr											
						0.5-1.0	1.0-3.0	3.0-5.0	>5.0	5-10	10-50	50-100	>100	2500-5000	5000-10000	>10000																								
8V3283RA/RJ	HL08-41	125967	114.00	116.00	2.00	0.02	1.0	1.87	54	147	<0.5	<5	3.45	2	11	14	50	4.25	<1	0.28	12	100	1194	<2	0.01	1	1147	14	1.28	<5	3	124	<5	<0.01	<10	<10	33	<10	115	2
8V3283RA/RJ	HL08-41	125968	116.00	117.73	1.73	0.03	1.5	1.43	90	142	<0.5	<5	3.63	2	13	17	77	4.53	<1	0.28	<10	0.69	1089	<2	0.01	1	1143	24	2.79	<5	2	129	<5	<0.01	<10	<10	27	<10	54	2
8V3283RA/RJ	HL08-41	125969	117.73	118.93	1.20	0.17	2.4	1.95	171	100	<0.5	<5	7.77	4	20	16	81	5.73	<1	0.18	<10	1.08	2021	<2	<0.01	1	948	20	3.01	<5	4	218	<5	<0.01	<10	16	49	<10	104	2
8V3283RA/RJ	HL08-41	125970	118.93	121.00	2.07	0.06	1.6	1.66	49	158	<0.5	<5	7.36	1	12	17	59	4.24	<1	0.25	<10	0.96	1841	<2	0.01	1	1044	19	1.77	<5	3	261	<5	0.01	<10	12	40	<10	60	2
8V3283RA/RJ	HL08-41	125971	121.00	123.00	2.00	0.05	1.7	1.64	51	132	<0.5	<5	5.50	1	15	18	87	4.30	<1	0.24	<10	1.04	1481	<2	0.01	2	1132	18	2.00	<5	3	201	<5	<0.01	<10	10	52	<10	42	2
8V3283RA/RJ	HL08-41	125972	123.00	124.32	1.32	0.09	3.1	1.40	70	153	<0.5	<5	4.71	2	11	16	63	4.04	<1	0.26	<10	0.82	1225	<2	0.01	1	1110	26	2.31	<5	3	185	<5	<0.01	<10	10	36	<10	51	2
8V3283RA/RJ	HL08-41	125973	124.32	125.67	1.35	0.06	1.9	1.73	89	71	<0.5	<5	3.19	3	17	10	43	4.55	<1	0.25	<10	1.02	1749	<2	0.01	2	1173	46	1.40	<5	4	166	<5	<0.01	<10	10	68	<10	109	2
8V3283RA/RJ	HL08-41	125974	125.67	127.13	1.46	0.10	1.5	1.76	190	79	<0.5	<5	3.46	4	20	12	39	5.00	<1	0.27	<10	0.97	1764	<2	0.01	3	1199	33	1.66	<5	4	161	<5	<0.01	<10	11	71	<10	74	2
8V3283RA/RJ	HL08-41	125975	Std	PM113			1.83	162.0	0.89	181	<0.5	<5	5.49	6	17	24	3534	3.58	<1	0.19	<10	0.68	60	0.03	32	512	234	1.31	204	2	180	<5	0.07	<10	<10	23	19	231	9	
HL08-42 - Zone: Annalise, Pad 30: 434958E,6223958N, Elev: 1170m, Az:001, Dip: -50, EOH: 143.29m																																								
8V3283RA/RJ	HL08-42	120751	2.82	3.94	1.12	0.64	3.7	1.21	84	111	<0.5	<5	2.45	5	13	10	42	3.89	<1	0.28	<10	0.46	1730	<2	0.01	3	1164	62	1.87	<5	2	51	<5	<0.01	<10	<10	16	<10	589	1
8V3283RA/RJ	HL08-42	120752	3.94	6.00	2.06	0.17	1.7	1.62	143	141	<0.5	<5	1.98	3	16	11	36	4.71	<1	0.31	10	0.65	1836	<2	0.02	3	1202	12	1.73	<5	2	43	<5	<0.01	<10	<10	24	<10	103	2
8V3283RA/RJ	HL08-42	120753	6.00	7.86	1.86	0.01	1.1	1.51	37	138	<0.5	<5	3.77	1	16	5	17	4.63	<1	0.29	<10	0.65	1993	<2	0.02	3	1243	9	1.94	<5	2	88	<5	<0.01	<10	11	25	<10	90	2
8V3283RA/RJ	HL08-42	120754	8.15	10.10	1.95	0.62	0.8	1.86	41	133	<0.5	<5	2.97	1	16	7	30	4.84	<1	0.27	<10	0.91	2144	<2	0.02	3	1215	6	1.22	<5	2	65	<5	<0.01	<10	10	35	<10	98	2
8V3283RA/RJ	HL08-42	120755	10.10	11.50	1.40	0.71	2.1	1.38	166	175	<0.5	<5	3.94	6	12	7	25	4.22	<1	0.29	<10	0.55	2202	<2	0.02	2	1111	122	1.57	<5	2	90	<5	<0.01	<10	11	24	<10	459	1
8V3633RA/RJ	HL08-42	122610	11.50	11.88	0.38	0.62	2.1	1.61	141	186	<0.5	<5	0.34	3	13	28	22	5.16	<1	0.24	10	0.67	1272	<2	0.02	2	1485	35	0.26	14	2	9	<5	<0.01	<10	<10	26	<10	387	2
8V3283RA/RJ	HL08-42	120756	11.88	12.91	1.03	0.07	1.4	1.86	46	135	<0.5	<5	2.57	1	15	7	28	4.83	<1	0.25	<10	0.90	1880	<2	0.02	3	1162	16	1.19	<5	2	61	<5	<0.01	<10	<10	39	<10	114	2
8V3283RA/RJ	HL08-42	120757	12.91	14.68	1.77	0.47	1.8	0.68	264	159	<0.5	<5	1.87	7	13	22	13	4.08	<1	0.30	<10	0.26	1004	<2	0.02	3	844	37	3.31	<5	2	61	<5	<0.01	<10	18	<10	201	2	
8V3283RA/RJ	HL08-42	120758	14.68	16.65	1.97	16.87	13.7	0.74	113	79	<0.5	<5	1.92	2	18	20	27	4.69	<1	0.32	<10	0.26	975	3	0.01	4	1075	20	4.61	<5	2	59	<5	<0.01	<10	<10	24	<10	54	2
8V3283RA/RJ	HL08-42	120759	16.65	18.64	1.99	0.44	3.3	1.31	147	88	<0.5	<5	3.95	4	23	10	100	5.50	<1	0.33	<10	0.69	1569	<2	0.01	3	1101	56	3.98	<5	3	123	<5	<0.01	<10	12	43	<10	165	2
8V3283RA/RJ	HL08-42	120760	18.64	20.63	1.99	0.14	1.8	2.87	51	156	<0.5	<5	4.60	<1	25	9	71	7.38	<1	0.36	<10	2.21	2475	<2	0.01	4	1386	17	1.90	<5	4	111	<5	0.01	<10	15	89	<10	93	2
8V3283RA/RJ	HL08-42	120761	20.63	22.03	1.40	0.36	1.8	1.33	79	119	<0.5	<5	3.47	2	25	19	46	4.68	<1	0.27	<10	0.80	1774	<2	0.01	10	1212	23	2.92	<5	3	118	<5	0.03	<10	12	44	<10	121	2
8V3283RA/RJ	HL08-42	120762	22.03	24.00	1.97	0.08	0.9	1.73	78	125	<0.5	<5	4.15	2	19	3	41	4.39	<1	0.25	<10	0.99	1739	<2	0.01	3	1132	8	0.86	<5	3	104	<5	<0.01	<10	<10	49	<10	62	2
8V3283RA/RJ	HL08-42	120763	24.00	26.00	2.00	0.70	1.5	1.83	197	138	<0.5	<5	4.12	7	20	4	47	4.68	<1	0.26	<10	0.98	1738	<2	0.01	3	1226	43	0.91	<5	3	96	<5	<0.01	<10	<10	53	<10	389	2
8V3283RA/RJ	HL08-42	120764	26.00	27.89	1.89	0.27	1.6	1.89	72	176	<0.5	<5	5.33	5	21	7	47	5.39	<1	0.31	<10	0.98	1980	<2	0.01	3	1247	49	1.99	<5	3	141	<5	0.02	<10	11	52	<10	511	2
8V3283RA/RJ	HL08-42	120765	27.89	29.89	2.00	0.34	3.5	2.31	44	133	<0.5	<5	4.56	2	24	5	67	5.74	<1	0.25	<10	1.27	2265	<2	0.02	3	1296	134	0.98	<5	4	126	<5	0.01	<10	11	72	<10	197	2
8V3633RA/RJ	HL08-42	122603	29.89	31.89	2.00	0.08	1.3	2.33	71	143	<0.5	<5	5.99	1	22	13	73	5.65	<1	0.26	10	1.38	2395	<2	0.02	2	1646	312	0.51	11	5	152	<5	0.02	<10	<10	81	<10	122	2
8V3633RA/RJ	HL08-42	122604	31.89	33.89	2.00	0.04	0.3	2.56	31	147	<0.5	<5	3.91	<1	26	12	49	6.55	<1	0.20	11	1.55	2277	<2	0.03	2	1785	35	0.59	12	6	107	<5	0.04	<10	<10	111	<10	151	3
8V3633RA/RJ	HL08-42	122605	33.89	35.89	2.00	0.01	0.2	2.71	20	141	<0.5	<5	4.19	1	25	10	52	6.65	<1	0.23	10	1.59	2317	<2	0.03	2	1840	36	0.65	12	6	145	<5	0.04	<10	<10	119	24	178	3
8V3633RA/RJ	HL08-42	122606	35.89	36.89	1.00	0.01	0.2	2.32	31	153	<0.5	<5	2.99	1	23	14	59	6.35	<1	0.22	<10	1.41	1995	<2	0.03	2	1824	37	0.97	11	5	109	<5	0.02	<10	<10	103	<10	240	3
8V3633RA/RJ	HL08-42	122607	36.89	38.75	1.86	<0.01	0.3	2.37	27	132	<0.5	<5	4.75	1	23	11	50	6.22	<1	0.17	<10	1.38	2250	<2	0.03	2	1732	30	0.65	12	6	140	<5	0.01	<10	<10	110	<10		

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3283RA/RJ	HL08-42	120805	138.92	140.63	1.71	0.01	0.7	1.46	26	172	<0.5	<5	5.45	1	29	3	69	5.71	<1	0.40	<10	1.13	1961	<2	0.02	5	1451	37	0.47	<5	8	207	<5	<0.01	<10	11	47	<10	117	2
8V3283RA/RJ	HL08-42	120806	140.63	142.02	1.39	<0.01	1.6	1.36	45	168	<0.5	<5	6.57	1	38	4	181	7.87	<1	0.40	<10	1.39	1990	<2	0.04	8	1468	47	0.73	<5	9	189	<5	<0.01	<10	20	53	<10	262	3
8V3283RA/RJ	HL08-42	120807	142.02	143.29	1.27	<0.01	0.5	0.90	29	130	<0.5	<5	6.13	<1	20	34	24	4.79	<1	0.29	<10	1.00	1990	<2	0.02	3	1106	38	0.43	<5	5	295	<5	<0.01	<10	12	28	<10	64	3
HL08-43 - Zone: Annalise, Pad 30: 434958E,6223958N, Elev: 1170m, Az: 031, Dip: -52, EOH: 71.95m																																								
8V3283RA/RJ	HL08-43	120808	2.13	3.50	1.37	0.30	1.3	1.62	40	124	<0.5	<5	2.19	1	18	6	8	4.89	<1	0.31	14	0.65	1953	<2	0.01	3	1426	19	2.17	<5	2	46	<5	<0.01	<10	<10	22	<10	104	2
8V3283RA/RJ	HL08-43	120809	3.50	5.54	2.04	0.16	2.9	1.32	101	173	<0.5	<5	1.42	2	19	16	24	4.64	<1	0.40	11	0.45	1789	<2	0.01	4	1380	23	2.94	<5	2	34	<5	<0.01	<10	<10	20	<10	110	2
8V3283RA/RJ	HL08-43	120810	5.54	6.70	1.16	0.07	1.8	1.61	33	168	<0.5	<5	1.92	1	17	8	31	4.91	<1	0.39	12	0.61	1325	<2	0.02	3	1523	14	2.50	<5	3	57	<5	<0.01	<10	<10	27	<10	118	2
8V3283RA/RJ	HL08-43	120811	6.70	7.90	1.20	0.02	1.0	1.69	38	150	<0.5	<5	2.69	1	17	9	12	4.18	<1	0.36	11	0.69	1929	<2	0.02	4	1480	8	1.33	<5	3	84	<5	<0.01	<10	<10	29	<10	89	1
8V3283RA/RJ	HL08-43	120812	7.90	9.90	2.00	<0.01	1.6	1.58	89	156	<0.5	<5	3.82	2	18	13	41	4.48	<1	0.32	10	0.67	2503	<2	0.03	4	1237	9	1.85	<5	3	104	<5	<0.01	<10	<10	30	<10	94	2
8V3283RA/RJ	HL08-43	120813	9.90	11.90	2.00	0.03	1.6	1.72	68	158	<0.5	<5	2.94	1	16	14	40	4.62	<1	0.32	11	0.72	2216	<2	0.02	6	1359	9	1.51	<5	3	73	<5	<0.01	<10	<10	32	<10	97	2
8V3283RA/RJ	HL08-43	120814	11.90	13.90	2.00	0.07	0.9	1.76	70	186	<0.5	<5	1.49	1	17	6	27	4.64	<1	0.34	10	0.70	1605	<2	0.01	3	1298	8	1.30	<5	2	43	<5	<0.01	<10	<10	30	<10	106	2
8V3283RA/RJ	HL08-43	120815	13.90	15.30	1.40	0.03	1.7	1.47	712	192	<0.5	<5	3.46	17	14	6	4	4.05	<1	0.28	<10	0.50	2325	<2	0.01	2	1024	10	1.51	<5	2	73	<5	<0.01	<10	<10	27	<10	66	1
8V3283RA/RJ	HL08-43	120816	15.30	16.03	0.73	0.11	2.2	1.17	165	152	<0.5	<5	1.62	4	12	10	5	4.09	<1	0.22	<10	0.40	1283	<2	0.02	2	810	14	2.01	5	2	44	<5	<0.01	<10	<10	23	<10	62	2
8V3283RA/RD	HL08-43	120817	16.03	17.50	1.47	5.75	3.9	0.83	261	86	<0.5	<5	1.48	7	12	22	14	3.49	<1	0.29	<10	0.21	761	<2	0.01	4	992	103	2.48	<5	1	48	<5	<0.01	<10	<10	13	<10	232	1
8V3283RA/RD	HL08-43	120818	17.50	19.00	1.50	0.22	2.1	1.02	282	143	<0.5	<5	2.13	7	15	20	18	4.17	<1	0.26	<10	0.29	1206	<2	0.01	3	1194	34	2.59	<5	1	59	<5	<0.01	<10	<10	18	<10	57	2
8V3283RA/RD	HL08-43	120819	19.00	19.80	0.80	0.27	5.3	0.71	325	46	<0.5	<5	3.14	8	22	19	39	4.43	<1	0.35	<10	0.18	1301	3	0.01	5	1189	32	4.35	<5	2	122	<5	<0.01	<10	<10	18	<10	41	2
8V3283RA/RD	HL08-43	120820	19.80	21.00	1.20	0.23	2.9	0.51	466	125	<0.5	<5	3.34	12	13	51	35	2.82	<1	0.18	<10	0.19	1180	3	0.01	3	642	54	2.34	<5	1	101	<5	<0.01	<10	<10	14	<10	100	1
8V3283RA/RD	HL08-43	120821	21.00	22.00	1.00	0.14	2.3	0.20	273	104	<0.5	<5	5.16	7	9	60	10	2.65	<1	0.15	<10	0.03	1158	2	0.01	4	351	46	2.88	<5	1	147	<5	<0.01	<10	<10	4	<10	81	1
8V3283RA/RD	HL08-43	120822	22.00	23.00	1.00	0.17	1.7	0.33	181	47	<0.5	<5	2.53	4	14	44	15	3.32	<1	0.21	<10	0.08	831	<2	0.01	4	683	15	3.44	<5	2	73	<5	<0.01	<10	<10	10	<10	22	1
8V3283RA/RD	HL08-43	120823	23.00	23.80	0.80	0.10	2.5	0.44	228	43	<0.5	<5	3.96	5	20	35	15	4.15	<1	0.26	<10	0.15	1350	<2	0.01	5	862	20	4.21	<5	2	137	<5	<0.01	<10	<10	14	<10	11	2
8V3283RA/RD	HL08-43	120824	23.80	25.80	2.00	0.25	2.9	1.42	315	153	<0.5	<5	3.42	8	21	16	67	6.7	<1	0.28	<10	0.73	1608	<2	0.01	4	1476	43	1.86	<5	2	99	<5	<0.01	<10	<10	38	<10	100	2
8V3283RA/RD	HL08-43	120825	Std	PM1110	1.88		160.0	0.93	230	207	<0.5	91	5.71	7	17	26	3739	3.75	5	0.18	<10	0.20	703	80	0.03	36	704	242	1.44	205	2	183	<5	0.08	<10	<10	25	27	249	11
8V3283RA/RD	HL08-43	120826	25.80	27.80	2.00	0.29	28.5	1.71	2236	137	<0.5	6	4.03	59	20	15	57	5.63	<1	0.31	<10	1.00	1929	<2	0.01	4	1729	143	2.14	<5	3	113	<5	<0.01	<10	<10	46	<10	481	2
8V3283RA/RD	HL08-43	120827	27.80	29.40	1.60	0.11	1.1	1.93	68	134	<0.5	7	5.73	1	20	11	40	5.30	<1	0.24	<10	1.04	2279	<2	0.01	4	1567	12	1.46	<5	3	154	<5	<0.01	<10	<10	55	<10	88	2
8V3283RA/RD	HL08-43	120828	29.40	31.00	1.60	0.02	1.1	2.09	56	177	<0.5	7	3.87	1	21	7	52	5.77	<1	0.30	<10	1.10	2059	<2	0.01	4	1807	12	1.07	<5	4	114	<5	<0.01	<10	<10	66	<10	93	2
8V3283RA/RD	HL08-43	120829	31.00	32.27	1.27	12.77	16.2	1.17	335	83	<0.5	6	6.27	66	16	18	184	5.19	2	0.22	<10	0.58	2392	<2	0.01	3	1247	2332	3.43	<5	2	143	<5	<0.01	<10	17	35	114	7162	2
8V3283RA/RD	HL08-43	120830	32.27	34.00	1.73	0.03	0.7	1.89	32	158	<0.5	7	6.80	1	21	10	46	5.30	<1	0.26	<10	0.97	2542	<2	0.02	4	1540	33	1.73	<5	3	139	<5	<0.01	<10	17	62	<10	162	2
8V3283RA/RD	HL08-43	120831	34.00	36.00	2.00	0.03	1.1	1.89	55	139	<0.5	6	4.69	1	22	10	42	5.37	<1	0.25	<10	1.02	1121	<2	0.01	4	1726	34	2.06	<5	3	123	<5	<0.01	<10	<10	60	<10	113	2
8V3283RA/RD	HL08-43	120832	36.00	38.00	2.00	0.03	1.1	2.22	68	136	<0.5	7	6.28	3	23	7	39	6.00	<1	0.29	<10	1.12	2764	<2	0.02	4	1794	88	2.48	<5	3	153	<5	<0.01	<10	15	65	<10	199	2
8V3283RA/RD	HL08-43	120833	38.00	40.00	2.00	0.02	1.0	2.25	30	132	<0.5	6	5.91	1	24	11	46	5.45	<1	0.28	<10	0.94	2791	<2	0.02	4	1823	20	1.20	<5	3	150	<5	<0.01	<10	14	58	<10	101	2
8V3283RA/RD	HL08-43	120834	40.00	41.90	1.90	0.04	7.6	2.36	28	164	<0.5	7	6.68	1	28	4	61	5.81	<1	0.33	<10	0.95	3242	<2	0.02	4	1490	72</												

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																										
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3298RA/RJ	HL08-44	120874A	38.50	40.50	2.00	0.33	2.0	2.21	123	149	<0.5	<5	7.47	3	27	28	65	7.87	<1	0.35	<10	1.26	2875	<2	0.01	4	1682	43	3.97	<5	4	149	<5	<0.01	<10	18	63	<10	170	3
8V3298RA/RJ	HL08-44	120875	Blank	Blank		0.01	<0.1	1.20	<5	330	<0.5	<5	0.72	<1	11	126	1	2.90	<1	0.63	10	0.85	285	<2	0.06	7	953	3	0.01	<5	3	55	5	0.15	<10	<10	53	<10	68	2
8V3298RA/RJ	HL08-44	120876	40.50	42.50	2.00	0.06	1.5	2.17	87	132	<0.5	<5	7.28	2	25	20	59	6.21	<1	0.29	10	1.25	2875	<2	0.02	5	1712	59	1.82	<5	4	146	<5	<0.01	<10	11	69	<10	145	2
8V3298RA/RJ	HL08-44	120877	42.50	44.51	2.01	0.02	1.2	2.64	42	131	<0.5	<5	7.65	1	27	18	40	7.21	<1	0.31	<10	1.39	3025	<2	0.02	4	1729	24	1.75	<5	4	156	<5	<0.01	<10	16	79	<10	175	2
8V3298RA/RJ	HL08-44	120878	44.51	46.51	2.00	0.05	1.5	2.13	83	145	<0.5	<5	7.16	2	31	18	71	7.16	<1	0.36	<10	1.13	2581	<2	0.01	4	1358	31	2.80	<5	4	145	<5	<0.01	<10	16	59	<10	104	2
8V3298RA/RJ	HL08-44	120879	46.51	48.51	2.00	0.07	1.6	1.71	104	137	<0.5	<5	8.13	2	27	24	46	5.96	<1	0.32	<10	0.97	2573	<2	0.01	4	1208	31	2.39	<5	4	207	<5	<0.01	<10	12	47	<10	110	2
8V3298RA/RJ	HL08-44	120880	48.51	50.33	1.82	0.01	0.8	2.36	61	130	<0.5	<5	8.04	1	29	18	46	6.21	<1	0.33	11	1.36	2433	<2	0.01	5	1700	9	1.34	<5	5	162	<5	<0.01	<10	12	60	<10	80	2
8V3298RA/RJ	HL08-44	120881	50.33	52.33	2.00	0.02	0.9	2.36	63	190	<0.5	<5	6.84	2	30	24	52	7.65	<1	0.31	<10	1.55	2243	<2	0.02	6	1674	29	2.98	<5	5	158	<5	<0.01	<10	15	68	<10	264	3
8V3298RA/RJ	HL08-44	120882	52.33	54.33	2.00	0.01	0.6	1.45	37	103	<0.5	<5	4.29	<1	19	15	29	4.98	<1	0.23	<10	0.96	1496	<2	0.01	3	1113	11	2.10	<5	4	104	<5	<0.01	<10	14	44	<10	52	2
8V3298RA/RJ	HL08-44	120883	54.33	56.33	2.00	0.03	0.8	2.07	24	105	<0.5	<5	4.44	<1	19	8	47	5.25	<1	0.21	<10	1.16	1965	<2	0.02	3	1093	83	0.69	<5	4	112	<5	<0.01	<10	11	66	<10	71	2
8V3298RA/RJ	HL08-44	120884	56.33	58.33	2.00	0.03	0.7	2.12	15	95	<0.5	<5	4.75	<1	20	8	51	5.44	<1	0.20	<10	1.22	2239	<2	0.02	3	1110	9	0.94	<5	4	135	<5	<0.01	<10	13	78	<10	109	2
8V3298RA/RJ	HL08-44	120885	58.33	60.37	2.04	0.01	0.6	1.94	23	112	<0.5	<5	5.19	<1	18	7	44	5.01	<1	0.24	<10	1.14	2006	<2	0.02	3	1170	40	1.14	<5	3	156	<5	<0.01	<10	12	69	<10	79	2
8V3298RA/RJ	HL08-44	120886	60.37	62.37	2.00	0.01	0.7	1.91	38	111	<0.5	<5	3.49	<1	18	8	36	4.98	<1	0.26	<10	1.08	1787	<2	0.02	3	1155	9	1.31	<5	3	95	<5	<0.01	<10	11	62	<10	79	2
8V3298RA/RJ	HL08-44	120887	62.37	64.40	2.03	0.04	1.2	2.11	57	133	<0.5	<5	4.69	<1	22	6	49	5.28	<1	0.29	<10	1.01	2112	<2	0.01	3	1001	17	0.96	<5	3	125	<5	<0.01	<10	13	61	<10	77	2
8V3298RA/RJ	HL08-44	120888	64.40	66.40	2.00	0.03	1.7	1.79	41	116	<0.5	<5	5.68	<1	19	9	57	4.66	<1	0.34	<10	0.81	2243	<2	0.01	2	826	70	1.10	<5	4	138	<5	<0.01	<10	14	54	<10	113	1
8V3298RA/RJ	HL08-44	120889	66.40	68.40	2.00	0.04	1.3	1.47	92	103	<0.5	<5	4.98	1	19	12	50	4.77	<1	0.31	<10	0.64	1683	<2	0.01	2	868	24	2.16	<5	3	104	<5	<0.01	<10	11	43	<10	52	2
8V3298RA/RJ	HL08-44	120890	68.40	70.42	2.02	0.13	2.3	1.06	143	108	<0.5	<5	3.35	3	17	27	46	3.92	<1	0.34	<10	0.38	1286	<2	0.01	3	802	25	2.10	<5	3	70	<5	<0.01	<10	<10	33	<10	51	2
8V3298RA/RJ	HL08-44	120891	70.42	72.42	2.00	0.04	0.8	1.41	77	110	<0.5	<5	4.62	1	18	12	46	4.28	<1	0.31	<10	0.69	1507	<2	0.01	2	870	21	1.58	<5	4	119	<5	<0.01	<10	10	46	<10	51	1
8V3298RA/RJ	HL08-44	120892	72.42	74.40	1.98	0.02	0.7	1.78	36	95	<0.5	<5	5.12	<1	21	11	48	4.88	<1	0.30	<10	0.87	1614	<2	0.01	2	988	11	1.08	<5	4	132	<5	<0.01	<10	11	59	<10	48	2
8V3298RA/RJ	HL08-44	120893	74.40	76.38	1.98	0.01	0.4	2.00	11	125	<0.5	<5	5.62	<1	20	7	49	4.92	<1	0.31	<10	0.91	1865	<2	0.01	2	1027	7	0.41	<5	5	159	<5	<0.01	<10	12	71	<10	57	2
8V3298RA/RJ	HL08-44	120894	76.38	78.38	2.00	0.02	0.4	1.87	17	116	<0.5	<5	4.80	<1	21	10	51	4.67	<1	0.29	<10	0.90	1601	<2	0.01	3	950	7	0.55	<5	4	140	<5	<0.01	<10	10	73	<10	67	2
8V3298RA/RJ	HL08-44	120895	78.38	80.39	2.01	0.01	0.6	1.62	20	132	<0.5	<5	3.54	<1	21	6	49	4.46	<1	0.27	<10	0.84	1588	<2	0.01	3	1038	10	0.80	<5	3	124	<5	<0.01	<10	10	58	<10	58	2
8V3298RA/RJ	HL08-44	120896	92.38	94.19	1.81	0.02	0.8	1.95	23	110	<0.5	<5	4.48	<1	20	6	92	4.67	<1	0.24	<10	1.15	1545	<2	0.02	2	1050	8	0.69	<5	4	158	<5	<0.01	<10	<10	72	<10	69	2
8V3298RA/RJ	HL08-44	120897	94.19	95.93	1.74	0.02	1.0	2.07	14	90	<0.5	<5	3.58	<1	20	5	100	4.98	<1	0.17	<10	1.31	1521	<2	0.03	2	1097	130	0.76	<5	5	126	<5	0.01	<10	<10	87	<10	186	2
8V3298RA/RJ	HL08-44	120898	102.54	104.54	2.00	0.02	0.5	1.94	12	100	<0.5	<5	3.48	<1	19	5	59	4.72	<1	0.22	<10	1.12	1034	<2	0.02	2	1122	5	0.76	<5	4	110	<5	<0.01	<10	<10	66	<10	69	2
8V3298RA/RJ	HL08-44	120899	104.54	106.54	2.00	0.01	0.6	2.02	17	108	<0.5	<5	3.75	<1	19	10	66	4.78	<1	0.24	<10	1.17	1068	<2	0.02	2	1268	6	0.69	<5	4	124	<5	<0.01	<10	<10	67	<10	72	2
8V3298RA/RJ	HL08-44	120900	Std	PM922		6.56	3.0	1.31	561	150	<0.5	<70	7.50	14	46	67	490	5.33	10	0.16	11	34	826	102	0.03	70	781	83	2.07	<5	3	111	<5	0.09	<10	<10	40	36	91	12
8V3298RA/RJ	HL08-44	120901	106.54	109.54	2.00	0.01	0.5	1.96	28	117	<0.5	<5	4.11	<1	19	7	48	4.90	<1	0.25	<10	1.12	1111	<2	0.02	2	1234	5	1.02	<5	4	129	<5	<0.01	<10	<10	67	<10	73	2
8V3298RA/RJ	HL08-44	120902	108.54	110.54	2.00	0.03	0.5	1.86	40	143	<0.5	<5	3.50	<1	20	6	45	4.95	<1	0.25	<10	1.05	1025	<2	0.02	2	1228	8	1.34	<5	4	123	<5	0.01	<10	<10	63	<10	72	2
8V3298RA/RJ	HL08-44	120903	110.54	112.54	2.00	0.03	0.3	1.99	20	157	<0.5	<5	4.23	<1	19	9	44	4.92	<1	0.23	<10	1.21	1087	<2	0.03	2	1226	5	0.92	<5	5	147	<5	0.01	<10	<10	73	<10	73	2
HL08-45 - Zone:Gerry's, Pad 31:																																								

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0					Ag: 5-10 10-50 50-100 >100					Pb/Zn: 2500-5000 5000-10000 >10000																										
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm	
8V3298RA/RJ	HL08-45	120945	77.20	78.70	1.50	0.55	2.1	2.03	5	38	<0.5	<5	2.79	3	19	20	556	4.03	<1	0.14	<10	1.25	1233	36	0.04	<1	1244	14	0.18	<5	3	79	<5	0.16	<10	<10	84	<10	372	5	
8V3298RA/RJ	HL08-45	120946	78.70	80.70	2.00	0.66	1.0	2.50	<5	43	<0.5	<5	3.08	<1	22	24	254	5.34	<1	0.13	<10	1.68	1412	14	0.03	1	1279	13	0.25	<5	4	66	<5	0.15	<10	<10	105	<10	248	3	
8V3298RA/RJ	HL08-45	120947	80.70	82.70	2.00	0.66	1.5	2.44	7	51	<0.5	<5	1.98	1	22	23	392	5.12	<1	0.19	<10	1.55	1208	25	0.04	1	1254	13	0.29	<5	4	52	<5	0.17	<10	<10	104	<10	272	3	
8V3298RA/RJ	HL08-45	120948	82.70	84.70	2.00	0.70	3.8	1.85	20	35	<0.5	<5	3.19	2	18	44	467	4.15	1	0.10	<10	1.18	1337	21	0.02	2	1148	20	0.30	<5	3	57	<5	0.14	<10	<10	83	<10	324	5	
8V3298RA/RJ	HL08-45	120949	84.70	86.00	1.30	0.51	2.5	1.95	14	41	<0.5	<5	4.00	1	20	29	635	4.66	1	0.13	<10	1.30	1534	18	0.02	1	1209	10	0.44	<5	5	104	<5	0.12	<10	<10	95	<10	230	4	
8V3298RA/RJ	HL08-45	120950	Blank	Blank	0.01	<0.1	0.95	<5	270	<0.5	<5	0.53	<1	9	115	4	2.34	1	0.48	<10	0.64	606	<2	0.05	6	803	4	<0.01	<5	2	45	5	0.13	<10	<10	44	<10	52	2		
8V3298RA/RJ	HL08-45	120951	86.00	87.20	1.20	0.52	1.3	2.05	8	50	<0.5	<5	2.42	1	20	26	281	4.48	1	0.19	<10	1.40	1176	30	0.02	1	1348	9	0.32	<5	4	66	<5	0.17	<10	<10	97	<10	209	3	
8V3298RA/RJ	HL08-45	120952	87.20	88.90	1.70	0.80	1.1	2.03	7	38	<0.5	<5	2.59	<1	20	44	204	4.44	<1	0.10	<10	1.44	1154	32	0.03	2	1244	9	0.26	<5	3	66	<5	0.15	<10	<10	93	<10	199	3	
8V3298RA/RJ	HL08-45	120953	88.90	90.45	1.55	0.53	2.6	2.07	52	56	<0.5	<5	3.41	2	21	21	217	5.13	1	0.15	<10	1.44	1759	18	0.02	1	1260	13	0.77	<5	5	66	<5	0.16	<10	<10	107	<10	208	4	
8V3298RA/RJ	HL08-45	120954	90.45	91.72	1.27	0.42	3.7	1.83	64	62	<0.5	<5	4.01	2	21	28	371	4.87	<1	0.19	<10	1.18	1586	20	0.02	1	1302	13	1.09	<5	5	64	<5	0.15	<10	<10	97	<10	177	4	
8V3298RA/RJ	HL08-45	120955	91.72	93.00	1.28	0.38	2.0	2.17	17	68	<0.5	<5	3.78	1	21	30	325	4.03	<1	0.15	<10	0.87	1348	25	0.02	1	1287	11	0.27	<5	3	125	<5	0.19	<10	<10	94	<10	169	5	
8V3298RA/RJ	HL08-45	120956	93.00	93.75	0.75	0.24	0.8	2.63	18	22	<0.5	<5	5.73	2	15	43	110	2.74	<1	0.04	<10	0.51	780	19	0.02	1	1249	5	0.10	<5	2	72	<5	0.12	<10	<10	71	13	139	11	
8V3298RA/RJ	HL08-45	120957	93.75	95.25	1.50	0.26	0.9	2.52	15	77	<0.5	<5	3.10	1	21	13	118	5.31	<1	0.13	<10	1.95	1459	20	0.02	1	1372	12	0.14	<5	6	91	<5	0.14	<10	<10	106	<10	180	4	
8V3298RA/RJ	HL08-45	120958	95.25	96.00	0.75	0.36	0.9	2.55	17	33	<0.5	<5	6.36	1	20	26	142	4.29	<1	0.10	<10	1.67	1199	16	0.02	1	1094	12	0.24	<5	4	136	<5	0.14	<10	<10	92	<10	162	3	
8V3298RA/RJ	HL08-45	120959	96.00	97.90	1.90	0.24	1.8	2.59	34	47	<0.5	<5	3.32	1	24	14	227	5.68	<1	0.14	<10	2.03	1568	9	0.03	1	1411	13	0.51	<5	6	80	<5	0.19	<10	<10	106	<10	184	3	
8V3298RA/RJ	HL08-45	120960	97.90	99.73	1.83	0.20	2.1	2.32	37	77	<0.5	<5	3.92	1	21	11	209	5.46	<1	0.23	<10	1.60	1775	10	0.02	1	1367	19	0.66	<5	5	75	<5	0.11	<10	<10	117	<10	199	3	
8V3298RA/RJ	HL08-45	120961	99.73	100.85	1.12	0.12	2.1	2.08	19	47	<0.5	<5	11.46	<1	17	11	173	4.74	<1	0.20	<10	1.34	3694	13	0.02	<1	1075	7	0.29	<5	4	345	<5	0.10	<10	<10	21	62	<10	116	2
8V3298RA/RJ	HL08-45	120962	100.85	101.46	0.61	0.39	1.4	1.59	14	20	<0.5	<5	6.30	<1	19	47	211	2.78	<1	0.06	<10	0.72	1000	7	0.02	2	1090	18	0.11	<5	4	246	<5	0.17	<10	<10	55	<10	100	2	
8V3298RA/RJ	HL08-45	120963	101.46	102.45	0.99	0.17	1.4	2.59	10	21	<0.5	<5	4.59	<1	23	16	206	5.22	<1	0.04	<10	1.91	1568	13	0.03	1	1279	15	0.13	<5	5	108	<5	0.18	<10	<10	94	15	163	4	
8V3298RA/RJ	HL08-45	120964	102.45	104.50	2.05	0.34	1.1	2.18	8	66	<0.5	<5	2.86	1	22	26	151	4.82	<1	0.17	<10	1.46	1348	17	0.03	1	1370	9	0.26	<5	4	72	<5	0.16	<10	<10	87	<10	179	3	
8V3298RA/RJ	HL08-45	120965	104.50	106.50	2.00	0.33	1.6	2.00	18	64	<0.5	<5	4.31	2	21	19	222	5.44	<1	0.17	<10	1.26	1514	12	0.02	1	1247	12	0.42	<5	5	93	<5	0.17	<10	<10	82	<10	290	3	
8V3298RA/RJ	HL08-45	120966	106.50	108.50	2.00	0.40	2.0	2.07	24	58	<0.5	<5	4.46	3	21	17	221	4.82	<1	0.17	<10	1.34	1726	19	0.02	1	1303	13	0.48	<5	4	71	<5	0.17	<10	<10	86	<10	343	4	
8V3298RA/RJ	HL08-45	120967	108.50	110.50	2.00	0.50	3.5	1.99	56	67	<0.5	<5	3.44	3	20	17	286	5.09	<1	0.22	<10	1.34	1453	21	0.02	1	1325	15	1.14	<5	4	85	<5	0.14	<10	<10	81	<10	236	3	
8V3298RA/RJ	HL08-45	120968	110.50	112.50	2.00	0.40	2.2	2.07	46	50	<0.5	<5	3.44	2	22	19	273	4.78	<1	0.13	<10	1.52	1522	21	0.02	1	1296	19	0.64	<5	4	91	<5	0.13	<10	<10	79	<10	251	3	
8V3298RA/RJ	HL08-45	120969	112.50	114.50	2.00	0.43	1.7	2.16	46	51	<0.5	<5	2.75	2	22	19	144	4.93	<1	0.13	<10	1.52	1534	9	0.03	1	1341	9	0.72	<5	4	90	<5	0.14	<10	<10	88	<10	194	3	
8V3298RA/RJ	HL08-45	120970	114.50	116.00	1.50	0.24	2.2	2.65	24	54	<0.5	<5	2.03	1	24	19	258	5.47	<1	0.12	<10	1.92	1492	32	0.04	2	1374	13	0.53	<5	5	95	<5	0.18	<10	<10	115	<10	241	4	
8V3298RA/RJ	HL08-45	120971	116.00	117.49	1.49	0.63	3.6	2.32	36	79	<0.5	<5	3.79	1	21	11	453	5.10	<1	0.19	<10	1.61	1669	32	0.03	1	1239	17	0.42	<5	5	128	<5	0.14	<10	<10	110	<10	294	4	
8V3298RA/RJ	HL08-45	120972	117.49	119.50	2.01	0.36	2.9	1.94	108	102	<0.5	<5	5.82	3	19	11	197	4.97	<1	0.35	<10	1.04	2126	23	0.02	1	1212	30	1.29	<5	4	140	<5	0.02	<10	<10	116	<10	238	2	
8V3298RA/RJ	HL08-45	120973	119.50	121.40	1.90	0.39	5.3	2.15	70	106	<0.5	<5	5.05	2	20	8	404	5.56	<1	0.36	<10	1.18	2163	44	0.02	1	1228	18	1.29	<5	4	110	<5	0.05	<10	<10	13	80	<10	294	2
8V3298RA/RJ	HL08-45	120974	121.40	123.35	1.95	0.51	4.2	2.57	76	131	<0.5	<5	4.61	2	31	6	319	7.38	<1	0.34	<10	1.29	2376	49	0.02	1	1195	23	1.58	<5	6	103	<5	0.03	<10	<1					

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3298RA/RJ	HL08-46	121016	72.33	74.00	1.67	0.06	1.4	1.03	42	59	<0.5	<5	>15.00	2	8	43	36	3.12	<1	0.15	<10	0.51	4590	2	0.01	2	648	26	0.80	<5	3	397	<5	<0.01	<10	17	34	<10	157	<1
8V3298RA/RJ	HL08-46	121017	74.00	75.35	1.35	0.14	2.8	1.36	204	90	<0.5	<5	4.49	8	11	62	69	4.26	<1	0.15	<10	0.81	2466	6	0.01	3	876	59	1.50	<5	3	128	<5	<0.01	<10	13	63	<10	425	1
8V3298RA/RJ	HL08-46	121018	75.35	76.46	1.11	0.36	2.9	1.51	344	79	<0.5	<5	8.36	11	15	34	102	5.17	<1	0.15	<10	0.86	3804	18	0.01	3	953	193	2.43	<5	3	222	<5	<0.01	<10	20	74	<10	381	1
8V3298RA/RJ	HL08-46	121019	76.46	77.83	1.37	0.34	5.2	1.85	381	85	<0.5	<5	5.91	38	17	42	247	6.39	<1	0.16	<10	1.18	3506	14	0.01	3	945	637	3.44	<5	4	125	<5	<0.01	<10	19	82	39	3195	2
8V3298RA/RJ	HL08-46	121020	77.83	79.58	1.75	0.26	3.3	1.31	362	116	<0.5	<5	3.24	30	15	55	116	4.83	<1	0.18	<10	0.74	2251	10	0.01	3	907	226	2.66	<5	3	91	<5	<0.01	<10	11	62	29	2447	2
8V3298RA/RJ	HL08-46	121021	79.58	80.88	1.30	0.24	3.7	1.69	317	112	<0.5	<5	3.88	8	16	28	222	5.41	<1	0.17	<10	0.88	2462	9	0.01	3	977	34	1.85	<5	4	87	<5	<0.01	<10	14	82	<10	126	1
8V3298RA/RJ	HL08-46	121022	80.88	81.68	0.80	0.37	24.5	1.27	103	93	<0.5	<5	3.02	106	23	51	1745	4.84	<1	0.15	<10	0.71	2085	8	0.01	3	809	3761	2.99	<5	2	115	<5	<0.01	<10	11	46	130	11000	1
8V3298RA/RJ	HL08-46	121023	81.68	82.93	1.25	0.23	3.7	1.83	253	112	<0.5	<5	3.46	27	16	53	200	5.72	<1	0.14	<10	1.18	3009	14	0.01	3	834	514	2.50	<5	3	77	<5	<0.01	<10	15	79	28	2369	2
8V3298RA/RJ	HL08-46	121024	82.93	84.25	1.32	0.21	1.8	1.48	240	90	<0.5	<5	3.97	7	12	27	63	4.9	<1	0.12	<10	0.78	2708	7	0.01	2	874	49	1.15	<5	4	84	<5	0.01	<10	11	87	<10	186	1
8V3298RA/RJ	HL08-46	121025	Std	PM1116		0.11	765.7	0.70	565	217	<0.5	87	0.63	24	8	21	8058	2.51	6	0.17	<10	0.60	334	522	0.03	6	409	1062	1.34	1590	2	83	<5	0.05	<10	<10	21	<10	1114	2
8V3298RA/RJ	HL08-46	121026	84.25	85.85	1.60	0.20	3.5	1.88	241	126	<0.5	<5	3.54	6	14	38	78	5.06	<1	0.16	<10	1.08	3028	28	0.01	3	1118	47	1.36	<5	4	89	<5	0.01	<10	15	90	<10	171	2
8V3298RA/RJ	HL08-46	121027	85.85	87.50	1.65	0.12	3.3	2.07	204	269	<0.5	<5	5.59	12	16	25	118	5.33	<1	0.20	<10	1.22	3270	7	0.01	3	1095	393	1.36	<5	4	132	<5	0.01	<10	17	78	12	947	2
8V3298RA/RJ	HL08-46	121028	87.50	88.83	1.33	0.11	3.5	2.12	183	94	<0.5	<5	4.82	16	14	20	158	5.45	<1	0.20	<10	1.24	3169	10	0.01	2	1094	123	1.49	<5	4	96	<5	<0.01	<10	17	84	19	1624	2
8V3298RA/RJ	HL08-46	121029	88.83	90.30	1.47	0.20	4.5	1.90	187	110	<0.5	<5	4.03	5	15	34	156	5.18	<1	0.21	<10	1.10	2870	7	0.01	3	1138	174	1.66	<5	3	126	<5	<0.01	<10	16	74	<10	151	2
8V3298RA/RJ	HL08-46	121030	90.30	91.73	1.43	0.12	3.2	2.09	164	97	<0.5	<5	5.67	9	16	23	142	5.34	<1	0.25	<10	1.19	3209	16	0.01	3	1228	474	1.73	<5	3	234	<5	<0.01	<10	18	75	<10	726	2
8V3298RA/RJ	HL08-46	121031	91.73	92.90	1.17	0.08	4.6	2.33	111	150	<0.5	<5	5.01	13	17	21	124	5.59	<1	0.25	<10	1.43	3152	8	0.01	3	1197	161	1.52	<5	3	129	<5	<0.01	<10	17	78	18	1430	2
8V3298RA/RJ	HL08-46	121032	92.90	93.70	0.80	1.65	238.4	2.61	289	83	<0.5	<5	3.91	35	17	26	257	8.55	<1	0.21	<10	1.76	3184	12	0.01	3	1166	4491	4.93	12	4	105	<5	<0.01	<10	22	81	42	3528	3
8V3298RA/RJ	HL08-46	121033	93.70	94.89	1.19	0.94	177.0	1.25	641	71	<0.5	<5	3.38	151	19	40	327	7.83	1	0.15	<10	0.67	2245	13	0.01	3	782	2648	>5.00	11	2	63	<5	0.01	<10	17	43	196	11600	3
8V3298RA/RJ	HL08-46	121034	94.89	96.65	1.76	0.19	5.4	1.39	96	100	<0.5	<5	2.86	8	12	38	137	4.23	<1	0.20	<10	0.68	1917	26	0.01	1	992	448	1.46	<5	2	63	<5	0.01	<10	<10	41	10	794	1
8V3298RA/RJ	HL08-46	121035	96.65	98.27	1.62	0.17	3.4	1.72	145	122	<0.5	<5	3.44	6	15	34	63	5.13	<1	0.27	<10	0.78	2080	7	0.01	2	1121	106	1.66	<5	2	64	<5	0.01	<10	<10	51	<10	357	2
8V3298RA/RJ	HL08-46	121036	98.27	99.70	1.43	0.19	2.2	1.29	172	69	<0.5	<5	4.97	5	12	39	54	4.25	<1	0.19	<10	0.64	2361	5	0.01	2	798	67	1.98	<5	2	69	<5	0.03	<10	14	43	<10	146	1
8V3298RA/RJ	HL08-46	121037	99.70	100.94	1.24	0.30	4.3	1.66	103	73	<0.5	<5	5.29	5	15	26	301	5.04	<1	0.22	<10	0.76	2032	39	0.01	1	1034	67	1.62	<5	3	100	<5	0.01	<10	10	51	<10	423	2
8V3298RA/RJ	HL08-46	121038	100.94	102.94	2.00	0.50	2.7	2.15	42	85	<0.5	<5	4.48	2	19	19	310	5.19	<1	0.21	<10	1.11	1998	23	0.01	1	1221	26	0.59	<5	4	89	<5	0.07	<10	12	86	<10	282	2
8V3298RA/RJ	HL08-46	121039	102.94	104.94	2.00	0.38	1.9	2.34	28	101	<0.5	<5	4.41	1	22	16	353	5.59	<1	0.22	<10	1.18	1844	23	0.02	1	1286	18	0.56	<5	4	104	<5	0.10	<10	11	84	<10	269	3
8V3298RA/RJ	HL08-46	121040	104.94	106.94	2.00	0.58	2.1	2.32	30	74	<0.5	<5	4.11	1	20	17	256	5.45	<1	0.23	<10	1.18	1796	68	0.02	1	1273	14	0.60	<5	5	86	<5	0.12	<10	10	94	<10	233	3
8V3298RA/RJ	HL08-46	121041	106.94	108.94	2.00	0.29	2.0	2.30	25	60	<0.5	<5	4.08	1	20	13	229	5.57	<1	0.19	<10	1.26	1813	25	0.02	1	1176	17	0.66	<5	5	96	<5	0.08	<10	11	96	<10	314	2
8V3298RA/RJ	HL08-46	121042	108.94	110.90	1.96	0.17	3.2	2.50	36	64	<0.5	<5	4.22	3	22	14	342	5.95	<1	0.25	<10	1.38	1861	39	0.03	1	1393	38	0.91	<5	5	136	<5	0.05	<10	12	99	<10	432	2
8V3298RA/RJ	HL08-46	121043	110.90	112.90	2.00	0.43	2.9	2.39	359	51	<0.5	<5	4.32	10	23	13	261	6.06	<1	0.21	<10	1.36	2060	56	0.02	1	1387	18	1.40	<5	4	104	<5	0.10	<10	12	90	<10	326	2
8V3298RA/RJ	HL08-46	121044	112.90	114.81	1.91	0.31	1.3	2.54	165	53	<0.5	<5	4.50	5	23	10	97	5.83	<1	0.16	<10	1.52	1948	37	0.03	1	1334	13	0.74	<5	6	106	<5	0.15	<10	10	113	<10	300	3
8V3298RA/RJ	HL08-46	121045	114.81	116.78	1.97	0.55	1.2	2.70	<5	74	<0.5	<5	3.27	<1	24	13	181	5.96	<1	0.14	<10	1.70	1616	58	0.03	1	1390	12	0.34	<5	6	85	<5	0.17	<10	10	121	<10	325	3
8V3298RA/RJ	HL08-46	121046	116.78	118.78	2.00	0.48	2.0	2.43	7	71	<0.5	<5	3.31	1	22	12	352	5.42	<1	0.21	<10	1.41	1700	80	0.03	1	1384	14	0.57	<5	5	87	<5	0.15	<10	10	101	<10	288	3
8V3298RA/RJ	HL08-46	121047	118.78	120.76	1.98	0.70	2.6	2.31	17	70	<0.5	<5	5.30	2	21	15	384	5.31	<1	0.23	<10	1.19	1858	166	0.02	1	1305	25	0.67	<5	4	172	<5	0.13	<10	12	82	<10	373	3
8V3298RA/RJ	HL08-46	121048	120.76	122.76	2.00	1.06	2.3	2.39	10	78	<0.5	<5	4.11	1	21	17	424	5.17	<1	0.24	<10	1.36	1675	86	0.02	1	1288	22	0.35	<5	5	84	<5	0.14	<10	<10	86	<10	311	3
8V3298RA/RJ	HL08-46	121049	122.76	124.09	1.33	0.61	1.9	2.20	<5	77	<0.5	<5	4.98	2	19	10	289	4.80	<1	0.23</																				

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm	
8V3298RA/RJ	HL08-46	121088	184.59	186.33	1.74	0.12	2.3	2.07	59	134	<0.5	<5	3.03	9	15	21	102	5.29	<1	0.29	11	122	2704	7	0.01	1	1207	583	1.12	<5	2	97	<5	<0.01	<10	14	53	15	1145	2	
8V3298RA/RJ	HL08-46	121089	186.33	187.39	1.06	0.21	4.4	1.62	54	120	<0.5	<5	4.61	41	12	25	144	4.55	<1	0.26	<10	1.08	3194	4	0.01	2	1018	1238	1.41	<5	2	92	<5	<0.01	<10	16	40	67	5490	1	
8V3298RA/RJ	HL08-46	121090	187.39	188.50	1.11	0.26	2.4	0.67	62	81	<0.5	<5	10.99	14	6	22	37	2.49	<1	0.14	10	0.60	4925	2	0.01	1	547	518	0.64	<5	2	210	<5	<0.01	<10	23	27	22	1713	<1	
8V3298RA/RJ	HL08-46	121091	188.50	189.25	0.75	0.27	5.2	0.89	159	52	<0.5	<5	9.14	14	8	32	112	4.39	<1	0.12	12	0.59	4193	2	0.01	1	571	1653	2.60	<5	2	159	<5	<0.01	<10	19	43	17	1426	1	
8V3298RA/RJ	HL08-46	121092	189.25	191.16	1.91	0.09	2.1	1.07	34	84	<0.5	<5	3.64	2	13	20	200	4.19	<1	0.26	<10	0.77	2257	5	0.01	3	1096	22	0.61	<5	3	94	<5	<0.01	<10	10	53	<10	264	1	
8V3298RA/RJ	HL08-46	121093	191.16	192.85	1.69	0.07	1.2	1.58	8	141	<0.5	<5	2.93	<1	14	12	158	4.34	<1	0.20	<10	0.99	1649	4	0.02	3	1222	21	0.23	<5	4	77	<5	0.01	<10	<10	69	<10	188	2	
8V3298RA/RJ	HL08-46	121094	192.85	194.88	2.03	0.65	3.1	1.69	28	94	<0.5	<5	3.11	1	15	14	162	4.42	<1	0.22	<10	0.85	1730	5	0.02	3	1106	765	0.90	<5	4	100	<5	0.06	<10	<10	68	<10	158	2	
8V3298RA/RJ	HL08-46	121095	194.88	195.75	0.87	0.24	17.9	1.53	79	80	<0.5	<5	3.69	8	17	21	255	5.44	<1	0.24	<10	0.79	2264	3	0.01	3	1125	12000	3.22	<5	3	75	<5	0.01	<10	12	62	<10	569	2	
8V3298RA/RJ	HL08-46	121096	195.75	197.75	2.00	0.48	2.7	2.16	39	106	<0.5	<5	4.24	2	20	21	165	5.32	<1	0.29	<10	1.10	2301	6	0.02	4	1447	64	1.01	<5	5	105	<5	0.11	<10	12	96	<10	238	3	
8V3298RA/RJ	HL08-46	121097	197.75	199.67	1.92	0.35	2.5	1.65	66	109	<0.5	<5	3.49	2	14	19	171	4.26	<1	0.24	10	0.88	2224	8	0.02	3	1098	72	0.75	<5	3	72	<5	0.02	<10	11	59	<10	181	2	
8V3298RA/RJ	HL08-46	121098	199.67	201.67	2.00	0.18	2.4	1.80	95	98	<0.5	<5	4.62	3	15	17	133	4.67	<1	0.27	10	1.02	2858	3	0.01	3	1273	20	1.14	<5	3	96	<5	0.01	<10	13	61	<10	190	1	
8V3298RA/RJ	HL08-46	121099	201.67	203.67	2.00	0.11	1.9	1.84	138	126	<0.5	<5	3.60	4	14	24	133	4.71	<1	0.31	12	0.96	2530	5	0.02	2	1348	29	0.83	<5	3	67	<5	0.04	<10	13	59	<10	197	2	
8V3298RA/RJ	HL08-46	121100	Blank	Blank	0.02	<0.1	1.09	<5	298	<0.5	<5	0.59	<1	10	142	2	2.41	<1	0.57	<10	0.66	699	<2	0.07	7	808	6	<0.01	<5	3	55	<5	0.14	<10	<10	45	<10	60	2		
8V3298RA/RJ	HL08-46	121101	203.67	205.67	2.00	0.09	1.9	1.85	146	114	<0.5	<5	6.16	4	14	12	95	4.50	<1	0.34	12	0.98	2978	6	0.01	1	1277	23	0.90	<5	3	112	<5	0.04	<10	15	47	<10	188	2	
8V3298RA/RJ	HL08-46	121102	205.67	207.67	2.00	0.10	1.7	1.59	41	108	<0.5	<5	7.57	1	14	16	126	4.29	<1	0.39	10	0.72	2582	7	0.01	2	1165	14	0.62	<5	2	122	<5	0.02	<10	<10	40	<10	181	1	
8V3298RA/RJ	HL08-46	121103	207.67	208.79	1.12	0.06	1.3	1.82	52	108	<0.5	<5	4.51	2	12	13	78	4.42	<1	0.39	10	0.97	2321	5	0.01	2	1123	14	0.63	<5	2	76	<5	<0.01	<10	11	41	<10	143	1	
8V3298RA/RJ	HL08-46	121104	208.79	210.36	1.57	0.37	1.1	1.65	1181	134	<0.5	<5	3.09	33	13	20	83	4.35	<1	0.34	11	0.83	2090	7	0.01	2	1056	12	0.42	<5	2	60	<5	0.01	<10	11	43	<10	155	1	
8V3298RA/RJ	HL08-46	121105	210.36	211.76	1.40	0.26	2.5	1.33	189	108	<0.5	<5	5.18	7	14	17	161	4.66	<1	0.25	<10	0.74	2430	19	0.01	3	992	38	1.19	<5	3	68	<5	<0.01	<10	<10	61	<10	318	1	
8V3298RA/RJ	HL08-46	121106	212.28	213.40	1.12	0.17	2.7	0.82	82	100	<0.5	<5	3.50	3	19	29	155	5.03	<1	0.32	<10	0.62	2269	10	0.01	4	1214	15	0.95	19	3	75	<5	<0.01	<10	11	51	<10	198	1	
8V3298RA/RJ	HL08-46	121107	213.40	215.85	2.45	0.31	2.3	0.78	71	101	<0.5	<5	3.76	2	20	17	209	4.55	<1	0.32	<10	0.64	2143	20	0.01	4	1232	16	0.63	15	3	94	<5	<0.01	<10	<10	43	<10	191	1	
8V3298RA/RJ	HL08-46	121108	215.85	217.57	1.72	0.22	4.0	0.59	434	225	<0.5	<5	4.05	12	12	36	147	3.64	<1	0.31	<10	0.56	2441	17	0.01	9	928	41	1.29	16	2	178	<5	<0.01	<10	11	22	<10	139	1	
8V3298RA/RJ	HL08-46	121109	217.57	219.57	2.00	0.11	2.5	0.96	343	89	<0.5	<5	4.13	9	12	25	115	3.28	<1	0.31	<10	0.71	2200	10	0.01	6	1009	20	0.80	6	2	111	<5	<0.01	<10	<10	28	<10	147	1	
8V3298RA/RJ	HL08-46	121110	219.57	221.13	1.56	0.30	3.7	1.64	86	121	<0.5	<5	4.33	3	20	19	216	5.06	<1	0.23	<10	1.12	2300	35	0.01	8	1192	15	0.77	<5	6	158	<5	<0.01	<10	<10	13	86	<10	222	2
8V3298RA/RJ	HL08-46	121111	221.13	223.10	1.97	0.27	2.9	0.89	57	512	<0.5	<5	10.66	2	15	19	149	3.84	<1	0.26	<10	0.78	3435	77	0.01	4	1033	42	0.71	5	4	435	<5	<0.01	<10	14	44	<10	193	1	
HL08-47 - Zone:Chalet, Pad 32: 435263E,622598N, Elev: 1265m, Dip: -60, EOH: 608.84m																																									
8V3298RA/RJ	HL08-47	130001	3.00	4.00	1.00	0.02	<0.1	1.91	24	108	<0.5	<5	4.76	<1	14	33	9	4.92	<1	0.15	16	1.31	1402	<2	0.02	2	1100	9	2.35	<5	3	73	<5	<0.01	<10	<10	35	<10	88	2	
8V3298RA/RJ	HL08-47	130002	4.00	5.00	1.00	0.02	<0.1	1.72	9	126	<0.5	<5	5.41	<1	11	25	7	4.30	<1	0.17	15	1.24	1478	3	0.02	2	1209	8	1.93	<5	3	90	<5	<0.01	<10	<10	31	<10	109	2	
8V3298RA/RJ	HL08-47	130003	11.65	13.23	1.58	0.01	<0.1	3.31	5	68	<0.5	<5	9.22	<1	6	120	1	2.46	<1	0.11	<10	0.13	1442	<2	0.01	3	454	7	1.74	<5	1	358	<5	<0.01	<10	<10	5	<10	23	1	
8V3298RA/RJ	HL08-47	130004	21.95	22.65	0.70	0.01	0.3	3.03	16	145	<0.5	<5	3.17	<1	15	24	11	5.56	<1	0.20	<10	2.04	1548	17	0.02	2	1281	8	1.09	<5	4	76	<5	<0.01	<10	<10	50	<10	128	2	
8V3298RA/RJ	HL08-47	130005	31.05	32.00	0.95	0.01	<0.1	2.00	12	111	<0.5	<5	4.83	<1	14	26	16	5.21	<1	0.18	16	1.35	1332	<2	0.01	2	1301	10	2.53	<5	3	119	<5	<0.01	<10	<10	36	<10	111	2	
8V3298RA/RJ	HL08-47	130006	39.65	40.50	0.85	0.01	0.2	1.47	15	117	<0.5	<5	5.62	<1	15	28	13	5.35	<1	0.22	15	0.88	1311	<2																	

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																											
					0.5-1.0	1.0-3.0	3.0-5.0	>5.0	5-10	10-50	50-100	>100	2500-5000	5000-10000	>10000	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Zr													
8V3672RA/RJ	HL08-47	122663	169.50	171.50	2.00	0.12	3.8	1.03	479	135	<0.5	<5	0.91	13	14	24	37	3.93	<1	0.39	<10	0.40	663	2	0.01	3	1090	65	2.45	<5	2	53	<5	<0.01	<10	<10	22	<10	107	2
8V3672RA/RJ	HL08-47	122664	171.50	172.50	1.00	0.13	2.9	1.68	664	175	<0.5	<5	2.17	18	24	24	76	4.78	<1	0.48	<10	0.70	1376	<2	0.01	5	1190	72	1.77	<5	3	94	<5	<0.01	<10	<10	51	<10	131	2
8V3672RA/RJ	HL08-47	122665	172.50	174.50	2.00	0.06	2.2	1.85	499	223	<0.5	<5	1.77	14	25	10	83	4.73	<1	0.43	<10	0.80	1606	9	0.01	3	1388	52	0.77	<5	4	74	<5	0.07	<10	<10	56	<10	96	2
8V3672RA/RJ	HL08-47	122666	174.50	176.50	2.00	0.05	1.7	1.82	351	291	<0.5	<5	2.06	10	23	13	70	4.31	<1	0.53	<10	0.68	1556	5	0.01	3	1435	38	0.69	<5	4	73	<5	0.09	<10	<10	58	<10	98	3
8V3374RA/RJ	HL08-47	130042	186.66	187.94	1.28	0.11	2.0	1.47	216	117	<0.5	<5	3.44	11	21	11	63	5.11	<1	0.29	<10	0.65	2058	4	0.01	2	1360	354	2.47	<5	3	210	<5	0.01	<10	<10	37	15	947	2
8V3374RA/RJ	HL08-47	130043	230.55	231.20	0.65	0.66	2.8	1.34	412	81	<0.5	<5	5.70	12	19	18	132	4.66	<1	0.26	<10	0.78	2430	6	0.01	2	1100	428	2.69	<5	3	233	<5	0.01	<10	<10	41	<10	415	2
8V3374RA/RJ	HL08-47	130044	231.20	232.70	1.50	0.24	1.5	1.63	236	93	<0.5	<5	3.82	6	24	15	158	5.12	<1	0.26	<10	0.99	1910	16	0.01	3	1441	87	2.42	<5	3	151	<5	0.02	<10	<10	53	<10	226	2
8V3672RA/RJ	HL08-47	122667	247.00	248.50	1.50	0.24	2.4	2.63	71	186	<0.5	<5	3.15	5	29	9	206	5.99	<1	0.42	<10	1.31	3373	18	0.01	5	1730	46	0.40	<5	4	79	<5	0.08	<10	13	79	<10	245	2
8V3374RA/RJ	HL08-47	130045	248.50	249.75	1.25	0.37	16.9	1.09	440	99	<0.5	<5	5.63	99	15	27	295	4.72	1	0.22	<10	0.50	2726	<2	0.01	3	870	4880	3.23	<5	2	160	<5	0.01	<10	17	47	115	7463	2
8V3374RA/RJ	HL08-47	130046	249.75	250.75	1.00	0.34	2.9	0.54	543	66	<0.5	<5	13.22	39	8	32	145	2.61	<1	0.14	10	0.26	5621	<2	0.01	2	429	124	1.90	<5	1	376	<5	<0.01	<10	27	18	40	2563	<1
8V3374RA/RJ	HL08-47	130047	250.75	251.75	1.00	1.71	45.9	1.45	421	60	<0.5	<5	11.82	332	8	56	987	6.00	2	0.07	<10	1.34	4178	<2	0.01	19	182	13700	>5.00	19	1	320	<5	<0.01	<10	26	39	437	27000	2
8V3374RA/RJ	HL08-47	130048	251.75	252.55	0.80	0.56	10.3	0.15	376	74	<0.5	<5	9.68	19	13	27	553	4.16	<1	0.11	<10	0.04	2179	10	0.01	2	649	301	4.57	<5	1	262	<5	<0.01	<10	10	4	17	1141	1
8V3672RA/RJ	HL08-47	122668	252.55	254.00	1.45	0.49	4.2	1.60	409	115	<0.5	<6	4.77	14	27	16	216	5.99	<1	0.45	<10	0.76	1530	38	0.01	4	1126	175	4.01	<5	3	124	<5	0.02	<10	<10	39	<10	314	3
8V3672RA/RJ	HL08-47	122669	254.00	255.50	1.50	0.33	6.1	1.36	484	100	<0.5	<6	5.32	13	21	14	281	6.34	<1	0.35	<10	0.65	1522	48	0.01	4	1211	62	4.61	<5	3	161	<5	<0.01	<10	<10	38	<10	130	3
8V3672RA/RJ	HL08-47	122670	255.50	257.00	1.50	0.49	5.5	1.37	470	122	<0.5	<7	3.82	13	26	16	149	5.66	<1	0.40	<10	0.56	1407	15	0.01	4	1313	110	3.97	<5	3	97	<5	0.01	<10	<10	37	<10	83	3
8V3374RA/RJ	HL08-47	130049	257.00	258.00	1.00	0.67	3.8	1.40	229	80	<0.5	<5	6.09	8	22	17	269	4.65	<1	0.26	<10	0.64	1790	49	0.01	3	1104	191	2.09	<5	4	173	<5	0.02	<10	<10	47	<10	405	2
8V3374RA/RJ	HL08-47	130050	Blank	Blank		0.01	<0.1	0.85	<5	256	<0.5	<5	0.35	<1	8	91	1	2.03	<1	0.47	<10	0.56	552	<2	0.05	6	795	27	0.01	<5	2	39	<5	0.14	<10	<10	38	<10	80	2
8V3374RA/RJ	HL08-47	130051	258.00	259.00	1.00	0.40	4.8	1.21	303	99	<0.5	<5	3.22	8	27	17	325	4.83	<1	0.31	<10	0.49	1231	13	0.01	4	1196	106	2.80	<5	2	101	<5	<0.01	<10	<10	38	<10	193	2
8V3672RA/RJ	HL08-47	122671	259.00	260.50	1.50	0.38	1.9	1.74	310	140	<0.5	<6	5.08	9	23	13	102	5.19	<1	0.49	<10	0.76	1384	2	0.01	3	1285	103	2.35	<5	4	127	<5	0.01	<10	<10	48	<10	134	2
8V3672RA/RJ	HL08-47	122672	260.50	262.00	1.50	0.17	2.9	1.79	209	134	<0.5	<6	5.64	7	24	14	77	4.61	1	0.44	<10	0.80	1887	5	0.01	3	1508	127	1.58	<5	3	130	<5	0.01	<10	<10	47	<10	124	2
8V3672RA/RJ	HL08-47	122673	262.00	263.50	1.50	0.20	2.7	1.72	290	124	<0.5	<6	5.17	8	22	11	97	5.12	<1	0.40	<10	0.65	1522	3	0.01	3	1505	51	2.19	<5	4	112	<5	<0.01	<10	<10	46	<10	86	2
8V3672RA/RJ	HL08-47	122674	263.50	265.00	1.50	0.07	1.8	2.07	124	133	<0.5	<6	6.22	4	21	14	69	4.91	<1	0.44	<10	0.94	2006	<2	0.01	2	1458	47	1.29	<5	4	143	<5	<0.01	<10	<10	57	<10	111	2
8V3672RA/RJ	HL08-47	122675	265.00	266.50	1.50	0.15	3.4	2.29	197	121	<0.5	<6	5.51	6	22	14	119	6.12	<1	0.38	<10	1.12	2256	26	0.01	2	1517	128	1.84	<5	4	123	<5	0.01	<10	<10	57	<10	95	3
8V3672RA/RJ	HL08-47	122676	266.50	268.00	1.50	0.11	1.5	2.80	131	136	<0.5	<7	5.64	4	23	8	76	6.09	1	0.45	<10	1.25	2359	2	0.01	4	1470	47	1.00	<5	4	129	<5	0.01	<10	10	65	<10	97	2
8V3672RA/RJ	HL08-47	122677	268.00	269.50	1.50	0.09	2.7	2.54	137	170	<0.5	<7	5.31	5	21	12	123	5.80	<1	0.37	<10	1.22	2119	8	0.01	3	1404	126	1.04	<5	4	139	<5	0.01	<10	12	66	<10	175	2
8V3672RA/RJ	HL08-47	122678	269.50	271.00	1.50	0.03	1.2	2.79	75	152	<0.5	<7	5.82	3	23	5	66	5.57	<1	0.50	<10	1.21	2186	<2	0.01	4	1509	48	0.44	<5	5	147	<5	0.01	<10	<10	65	<10	92	2
8V3672RA/RJ	HL08-47	122679	271.00	272.50	1.50	0.11	2.6	2.53	87	146	<0.5	<7	5.43	3	23	6	135	6.06	<1	0.44	<10	0.96	2026	6	0.01	3	1546	82	1.20	<5	4	134	<5	<0.01	<10	11	62	<10	102	2
8V3672RA/RJ	HL08-47	122680	272.50	274.00	1.50	0.33	5.3	2.27	93	145	<0.5	<6	7.04	4	20	6	319	5.28	<1	0.46	<10	0.82	2066	25	0.01	2	1557	49	0.93	<5	4	220	<5	<0.01	<10	<10	62	<10	144	2
8V3672RA/RJ	HL08-47	122681	274.00	275.00	1.00	0.26	3.0	2.27	154	173	<0.5	<7	6.08	5	20	9	154	5.20	<1	0.53	<10	0.86	2077	18	0.01	3	1591	87	1.10	<5	5	146	<5	<0.01	<10	<10	58	<10	127	2
8V3672RA/RJ	HL08-47	122682	275.00	276.00	1.00	0.25	3.5	1.93	63	146	<0.5	<6	5.49	7	19	8	221	4.31	<1	0.46	<10	0.81	1962	57	0.01	2	1495	50	0.84	<5	4	141	<5	<0.01	<10	<10	48	<10	520	2
8V3672RA/RJ																																								

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:				2500-5000				5000-10000				>10000															
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3672RA/RJ	HL08-47	122757	364.20	365.70	1.50	0.06	0.8	2.31	70	175	<0.5	6	4.10	3	19	8	24	5.59	<1	0.45	<10	1.49	1956	<2	0.01	1	1687	36	0.99	<5	3	139	<5	0.01	<10	<10	57	<10	53	3
8V3672RA/RJ	HL08-47	122758	365.70	366.90	1.20	0.13	1.1	2.21	66	133	<0.5	7	4.65	3	20	10	39	5.73	<1	0.35	<10	1.40	2105	<2	0.01	1	1652	28	1.07	<5	2	156	<5	0.01	<10	<10	62	<10	54	2
8V3395RA/RJ	HL08-47	130069	366.90	367.95	1.05	0.08	1.4	2.18	89	103	<0.5	<5	3.85	5	17	8	24	5.45	<1	0.24	<10	1.48	2122	<2	0.01	1	1550	140	1.07	<5	2	128	<5	<0.01	<10	13	58	<10	380	2
8V3672RA/RJ	HL08-47	122759	367.95	369.40	1.45	0.04	1.1	2.09	53	170	<0.5	7	2.68	2	19	6	41	5.56	<1	0.41	<10	1.51	1647	<2	0.01	1	1659	30	1.04	<5	2	85	<5	<0.01	<10	<10	55	<10	45	2
8V3672RA/RJ	HL08-47	122760	369.40	370.90	1.50	0.06	1.1	2.34	98	233	<0.5	6	5.99	4	18	9	41	5.08	<1	0.38	<10	1.21	2165	<2	0.01	1	1684	32	0.87	<5	2	167	<5	<0.01	<10	<10	39	<10	109	2
8V3672RA/RJ	HL08-47	122761	370.90	371.90	1.00	0.06	0.9	0.92	257	407	0.5	7	4.32	7	19	4	26	5.62	<1	0.39	<10	0.95	1975	<2	0.01	1	1529	25	1.02	<5	3	153	<5	<0.01	<10	<10	28	<10	66	2
8V3672RA/RJ	HL08-47	122762	371.90	373.00	1.10	0.16	1.8	0.63	444	170	<0.5	6	4.96	12	19	10	44	5.41	<1	0.37	<10	0.73	2037	<2	0.01	2	1491	30	2.03	<5	3	175	<5	<0.01	<10	<10	22	<10	54	2
8V3395RA/RJ	HL08-47	130070	373.00	374.35	1.35	0.05	0.7	1.36	251	104	<0.5	<5	4.11	5	15	7	26	4.84	<1	0.28	<10	0.95	1916	<2	0.01	1	1603	26	1.14	<5	2	120	<5	<0.01	<10	<10	38	<10	64	2
8V3395RA/RJ	HL08-47	130071	374.35	375.00	0.65	0.27	2.3	0.68	185	118	<0.5	<5	3.47	11	10	31	39	3.49	<1	0.22	<10	0.39	1646	5	0.01	1	970	501	2.41	<5	1	118	<5	<0.01	<10	<10	19	17	1196	1
8V3395RA/RJ	HL08-47	130072	375.00	376.00	1.00	0.20	1.7	0.30	208	92	<0.5	<5	2.96	5	11	32	97	2.93	<1	0.19	<10	0.16	1683	26	0.01	2	844	69	2.83	<5	1	112	<5	<0.01	<10	<10	8	<10	197	1
8V3395RA/RJ	HL08-47	130073	376.00	377.00	1.00	0.27	3.3	0.37	249	80	<0.5	<5	2.74	5	13	55	165	4.01	<1	0.21	<10	0.17	1682	14	0.01	4	742	49	3.82	<5	1	95	<5	<0.01	<10	<10	10	<10	148	2
8V3395RA/RJ	HL08-47	130074	377.00	378.00	1.00	0.26	3.8	0.49	255	77	<0.5	<5	5.72	6	11	45	170	3.11	<1	0.20	<10	0.28	2810	47	0.01	3	868	39	2.29	<5	1	164	<5	<0.01	<10	16	16	<10	179	1
8V3395RA/RJ	HL08-47	130075	Std	PM1116		0.12	797.4	0.58	561	162	<0.5	80	0.51	20	7	19	7541	2.21	6	0.14	<10	0.56	277	540	0.03	5	528	904	1.18	1668	1	73	<5	0.04	<10	<10	16	<10	902	2
8V3395RA/RJ	HL08-47	130076	378.00	379.00	1.00	0.32	6.3	0.78	336	93	<0.5	<5	3.33	8	17	39	320	4.59	<1	0.24	<10	0.47	2692	50	0.01	4	1181	54	3.20	<5	1	129	<5	<0.01	<10	17	26	<10	304	1
8V3395RA/RJ	HL08-47	130077	379.00	380.00	1.00	0.43	5.4	0.38	442	71	<0.5	<5	3.35	9	20	33	217	5.98	<1	0.25	<10	0.18	2008	146	0.01	4	1657	53	5.00	<5	1	160	<5	<0.01	<10	11	12	<10	163	2
8V3395RA/RJ	HL08-47	130078	380.00	381.50	1.50	0.38	10.8	0.41	442	70	<0.5	<5	3.74	9	18	36	258	5.64	<1	0.28	<10	0.33	2523	56	0.01	4	1545	128	4.97	<5	2	119	<5	<0.01	<10	18	19	<10	212	2
8V3395RA/RJ	HL08-47	130079	381.50	383.00	1.50	0.19	6.6	0.61	275	77	<0.5	<5	4.03	8	14	30	326	4.61	<1	0.20	<10	0.40	3010	75	0.01	3	1444	309	3.43	<5	2	122	<5	<0.01	<10	18	32	<10	481	1
8V3395RA/RJ	HL08-47	130080	383.00	384.50	1.50	0.22	5.7	0.80	203	88	<0.5	<5	2.75	5	15	25	385	4.60	<1	0.23	<10	0.45	2647	56	0.01	3	1699	36	3.17	<5	2	86	<5	<0.01	<10	16	39	<10	251	1
8V3395RA/RJ	HL08-47	130081	384.50	386.00	1.50	0.16	3.0	0.38	260	72	<0.5	<5	3.33	6	16	30	157	3.82	<1	0.21	<10	0.18	1940	22	0.01	4	1218	44	3.59	<5	1	116	<5	<0.01	<10	<10	16	<10	150	1
8V3395RA/RJ	HL08-47	130082	386.00	387.50	1.50	0.43	4.9	0.39	218	54	<0.5	<5	3.84	5	13	41	211	3.56	<1	0.18	<10	0.29	2455	136	0.01	1	1022	68	2.90	<5	2	142	<5	<0.01	<10	11	15	<10	210	1
8V3395RA/RJ	HL08-47	130083	387.50	388.60	1.10	0.49	4.0	0.91	537	71	<0.5	<5	2.38	12	19	28	219	3.58	<1	0.21	<10	0.54	1921	142	0.01	2	1601	67	3.67	<5	2	94	<5	<0.01	<10	37	<10	245	2	
8V3395RA/RJ	HL08-47	130084	388.60	389.80	1.20	0.25	2.9	1.89	340	82	<0.5	<5	2.78	7	24	16	173	6.60	<1	0.21	<10	0.32	2553	65	0.01	3	1942	42	2.30	<5	4	119	<5	<0.01	<10	13	84	<10	260	3
8V3395RA/RJ	HL08-47	130085	389.80	391.00	1.20	0.41	2.4	1.42	199	116	<0.5	<5	6.39	4	21	22	143	5.33	<1	0.18	<10	1.25	3111	98	0.01	3	1621	28	1.45	<5	5	247	<5	<0.01	<10	19	68	<10	161	2
8V3395RA/RJ	HL08-47	130086	393.80	394.50	0.70	0.51	2.3	1.55	247	62	<0.5	<5	7.59	7	19	15	117	5.29	<1	0.20	<10	0.99	3539	63	0.01	3	1683	33	2.31	<5	4	281	<5	<0.01	<10	21	71	<10	379	2
8V3395RA/RJ	HL08-47	130087	396.85	397.85	1.00	0.52	1.9	1.67	250	162	<0.5	<5	9.16	5	18	17	133	5.04	<1	0.27	<10	0.98	3127	40	0.01	2	1484	25	1.88	<5	4	249	<5	<0.01	<10	19	68	<10	130	2
8V3395RA/RJ	HL08-47	130088	414.52	415.70	1.18	0.22	0.9	1.22	756	129	<0.5	<5	8.11	16	15	14	43	4.36	<1	0.36	<10	0.63	3248	2	0.01	2	1486	94	1.83	<5	3	344	<5	<0.01	<10	18	52	<10	166	1
8V3395RA/RJ	HL08-47	130089	415.70	416.90	1.20	0.11	0.6	1.32	133	124	<0.5	<5	11.58	3	15	11	28	3.93	<1	0.40	<10	0.64	4029	4	0.01	1	1404	69	1.29	<5	3	997	<5	<0.01	<10	22	36	<10	107	1
8V3395RA/RJ	HL08-47	130090	423.80	425.52	1.72	0.30	1.9	1.08	346	108	<0.5	<5	5.37	7	18	22	57	4.39	<1	0.39	<10	0.41	2396	5	0.01	4	1418	175	2.95	<5	2	160	<5	<0.01	<10	10	32	<10	121	2
8V3395RA/RJ	HL08-47	130091	425.52	426.45	0.93	0.14	1.2	1.84	229	146	<0.5	<5	2.93	5	19	6	71	4.99	<1	0.46	<10	0.84	1789	<2	0.01	3	1871	44	1.55	<5	3	84	<5	<0.01	<10	<10	48	<10	124	2
8V3395RA/RJ	HL08-47	SK130092	435.35	440.00	4.65	0.04	0.4	1.94	103	94	<0.5	<5	6.87	2	21	9	40	4.65	<1	0.39	<10	1.02	2941	<2	0.02	3	1614	31	0.79	<5	3									

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3497RA/RJ	HL08-47	130135	524.50	526.00	1.50	0.49	1.6	2.17	1395	119	<0.5	6	8.29	30	28	33	120	5.99	<1	0.26	<10	1.78	2387	<2	0.01	11	1970	414	2.02	<5	6	170	<5	0.01	<10	13	99	<10	353	2
8V3497RA/RJ	HL08-47	130136	526.00	527.20	1.20	0.05	0.6	1.72	194	118	<0.5	5	6.77	10	24	43	75	4.60	<1	0.24	<10	1.31	2265	<4	0.01	11	1813	128	1.28	<5	5	140	<5	0.01	<10	10	75	12	772	2
8V3497RA/RJ	HL08-47	130137	527.20	528.22	1.02	0.05	0.7	1.95	142	113	<0.5	6	6.32	9	20	28	82	4.81	<1	0.23	<10	1.52	2137	<2	0.01	9	1804	31	1.13	<5	5	126	<5	0.01	<10	10	81	12	725	2
8V3497RA/RJ	HL08-47	130138	528.22	530.00	1.78	0.08	1.5	1.90	172	105	<0.5	7	7.72	26	23	31	119	5.38	<1	0.23	<10	1.38	2597	<2	0.01	10	1650	538	1.65	<5	6	164	<5	0.01	<10	16	86	37	2390	2
8V3497RA/RJ	HL08-47	130139	533.00	534.45	1.45	0.07	1.3	2.33	684	109	<0.5	7	6.93	17	32	50	95	6.68	<1	0.21	<10	2.12	2697	<2	0.01	16	1779	88	2.44	<5	8	143	<5	0.01	<10	13	127	<10	449	2
8V3497RA/RJ	HL08-47	130140	534.45	535.00	0.55	0.05	1.5	1.34	452	86	<0.5	7	12.32	73	17	42	137	4.10	<1	0.17	<10	1.04	2873	<2	0.01	9	1113	147	1.83	<5	7	231	<5	<0.01	<10	14	78	91	5865	1
8V3497RA/RJ	HL08-47	130141	535.00	536.50	1.50	0.01	1.1	2.47	239	109	<0.5	6	7.18	17	31	63	118	6.67	<1	0.18	<10	2.42	1927	<2	0.01	17	1723	56	2.48	<5	10	143	<5	0.01	<10	10	159	16	944	3
8V3497RA/RJ	HL08-47	130142	536.50	538.00	1.50	0.01	0.4	2.42	111	86	<0.5	6	5.75	3	27	57	66	5.85	<1	0.12	<10	2.75	1621	<2	0.02	15	1715	24	1.82	<5	11	127	<5	0.01	<10	<10	168	<10	184	2
8V3497RA/RJ	HL08-47	130143	538.00	539.50	1.50	0.01	0.7	3.10	83	74	<0.5	7	5.18	3	31	76	91	7.29	<1	0.09	<10	3.68	1872	<2	0.02	18	1726	63	2.03	<5	14	118	<5	0.01	<10	10	210	<10	256	3
8V3497RA/RJ	HL08-47	130144	539.50	541.00	1.50	0.01	0.5	2.34	82	78	<0.5	6	5.83	3	28	67	76	6.53	1	0.09	<10	2.86	1823	<2	0.02	16	1692	85	2.68	<5	13	146	<5	0.01	<10	<10	195	<10	285	3
8V3497RA/RJ	HL08-47	130145	541.00	542.50	1.50	0.01	0.4	2.66	124	77	<0.5	5	5.19	3	31	64	80	6.76	<1	0.11	<10	3.30	1803	<2	0.02	17	1665	29	2.29	<5	13	137	<5	0.02	<10	10	191	<10	201	3
8V3497RA/RJ	HL08-47	130146	542.50	544.00	1.50	0.01	0.7	2.34	202	72	<0.5	<5	4.09	8	26	57	68	5.27	<1	0.09	<10	2.92	1608	<2	0.01	13	1508	123	1.64	<5	10	99	<5	0.04	<10	<10	161	<10	503	2
8V3497RA/RJ	HL08-47	130147	544.00	545.50	1.50	<0.01	0.3	2.55	127	63	<0.5	<5	3.76	3	28	58	61	6.01	<1	0.06	<10	3.19	1647	<2	0.01	13	1605	18	1.91	<5	13	87	<5	0.05	<10	10	195	<10	179	3
8V3497RA/RJ	HL08-47	130148	545.50	546.75	1.25	0.03	0.4	2.21	879	100	<0.5	5	4.18	18	29	57	67	5.79	<1	0.06	<10	2.59	1639	<2	0.01	15	1485	31	1.98	<5	12	92	<5	0.01	<10	<10	191	<10	179	3
8V3497RA/RJ	HL08-47	130149	546.75	548.00	1.25	0.05	0.5	2.02	1782	81	<0.5	6	5.86	36	25	55	63	5.53	<1	0.09	<10	2.19	1936	<2	0.01	14	1460	32	2.06	<5	9	121	<5	0.01	<10	<10	155	<10	121	2
8V3497RA/RJ	HL08-47	130150	Blank	Blank	0.01	<0.1	0.92	16	248	<0.5	<5	0.59	<1	8	101	2	2.19	<1	0.35	<10	0.65	590	<2	0.06	6	810	3	0.04	<5	2	41	<5	0.13	<10	<10	42	<10	56	2	
8V3497RA/RJ	HL08-47	130151	548.00	549.00	1.00	0.04	0.5	2.22	945	57	<0.5	6	6.25	23	23	61	68	5.82	<1	0.07	<10	2.37	2277	<2	0.01	13	1399	129	1.77	<5	11	128	<5	0.01	<10	11	171	10	581	2
8V3497RA/RJ	HL08-47	130152	549.00	550.00	1.00	0.02	0.5	2.36	129	68	<0.5	6	5.50	3	29	57	73	6.22	<1	0.07	<10	2.62	2116	<2	0.01	13	1546	66	2.03	<5	12	132	<5	0.01	<10	12	200	<10	162	3
8V3497RA/RJ	HL08-47	130153	550.00	551.50	1.50	0.07	1.5	1.81	1144	54	<0.5	7	7.19	71	20	55	128	5.65	<1	0.09	<10	1.71	2280	<2	0.01	12	1280	1245	2.33	<5	8	166	<5	0.01	<10	14	124	72	4667	2
8V3497RA/RJ	HL08-47	130154	551.50	553.00	1.50	0.02	0.3	2.42	310	104	<0.5	6	4.92	7	28	59	81	6.27	<1	0.09	<10	2.63	1885	<2	0.01	14	1480	110	1.84	<5	11	106	<5	0.01	<10	10	178	<10	207	3
8V3497RA/RJ	HL08-47	130155	553.00	554.50	1.50	0.03	2.9	2.65	351	52	<0.5	6	5.85	45	24	70	206	6.61	<1	0.05	<10	2.71	2435	<2	0.01	13	1394	2178	1.74	<5	14	145	<5	0.01	<10	12	195	59	3800	3
8V3497RA/RJ	HL08-47	130156	554.50	556.00	1.50	0.02	0.4	2.52	127	62	<0.5	5	6.27	7	24	71	78	5.80	<1	0.06	<10	2.57	2156	<2	0.01	13	1533	199	0.95	<5	15	135	<5	0.02	<10	10	209	10	592	2
8V3497RA/RJ	HL08-47	130157	556.00	557.45	1.45	0.02	0.9	2.16	145	56	<0.5	6	6.88	69	23	60	211	5.70	<1	0.05	<10	2.13	2267	<2	0.01	12	1275	343	1.69	<5	13	148	<5	0.02	<10	12	174	101	6458	2
8V3497RA/RJ	HL08-47	130158	557.45	558.25	0.80	0.01	0.3	2.34	87	55	<0.5	5	5.76	14	27	74	90	5.78	1	0.05	<10	2.59	2036	<2	0.01	15	1536	32	1.27	<5	15	141	<5	0.01	<10	11	208	21	1319	2
8V3497RA/RJ	HL08-47	130159	558.25	559.30	1.05	0.02	2.6	2.48	399	61	<0.5	6	6.69	46	25	65	229	6.02	<1	0.07	<10	2.50	2380	<2	0.01	14	1448	970	1.28	<5	13	140	<5	0.02	<10	11	178	56	3692	2
8V3497RA/RJ	HL08-47	130160	559.30	560.40	1.10	0.01	0.4	2.14	106	65	<0.5	<5	6.45	5	22	60	68	5.05	<1	0.07	<10	2.22	2011	<2	0.01	12	1390	19	0.90	<5	11	138	<5	0.05	<10	10	162	<10	354	2
8V3497RA/RJ	HL08-47	130161	560.40	562.00	1.60	0.01	0.8	2.44	400	64	<0.5	<5	5.42	11	27	68	84	5.69	<1	0.06	<10	2.64	1917	<2	0.01	14	1463	122	1.01	<5	14	124	<5	0.05	<10	10	193	<10	397	3
8V3497RA/RJ	HL08-47	130162	562.00	563.50	1.50	0.08	0.9	2.47	1585	55	<0.5	<5	4.86	31	26	68	68	5.83	<1	0.05	<10	2.82	1829	<2	0.01	14	1439	20	1.44	<5	13	124	<5	0.07	<10	10	191	<10	109	3
8V3497RA/RJ	HL08-47	130163	563.50	565.00	1.50	0.01	0.4	2.23	160	56	<0.5	<5	4.75	3	28	60	76	5.63	1	0.04	<10	2.55	1568	<2	0.01	13	1541	6	1.62	<5	15	120	<5	0.07	<10	<10	216	<10	81	3
8V3497RA/RJ	HL08-47	130164	565.00	566.90	1.90	0.02	0.7	2.54	141	64	<0.5	<5	3.97	2	29	67	82	6.35	<1	0.05	<10	2.73	1708	<2	0.02	15	1606	14	1.64	<5	15	99	<5	0.10	<10	<10	204	<10	112	4
8V3497RA/RJ	HL08-47	130165	566.90	568.00	1.10	0.16	4.3	1.88	4674	61	<0.5	<5	4.53	96	27	52	76	6.21	<1	0.05	<10	1.96	1787	<2	0.01	14	1556	351	2.69	21	12	120	<5	0.05	<10	12	177	12	734	3
8V3497RA/RJ	HL08-47	130166	568.00	569.50	1.50	<0.01	0.6	2.02	341	57	<0.5	<5	4.12	6	26	56	67	5.58	<1	0.05	<10	2.14	1658	<2	0.02	12	1513	9	1.85	<5	11	109	<5	0.10	<10	165	<10	96	3	
8V3497RA/RJ	HL08-47	130167	569.50	571.00	1.50	0.06	0.5	2.10	361	68	<0.5	<5	4.49	7	28	61	75	5.64	<1	0.08	<10	2.24	1665	<2	0.01	13	1497	16	1.83	<5	12	119	<5	0.09	<10	<10	173	<10	85	3
8V3497RA/RJ	HL08-47	130168	571.00	572.50	1.50	0.02	0.5	2.88	2542	68																														

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3374RA/RJ	HL08-48	121119	28.25	29.52	1.27	0.01	0.5	1.32	10	113	<0.5	<5	7.34	<1	12	46	8	4.70	<1	0.18	<10	0.91	1894	<2	0.02	3	1172	17	3.12	<5	4	239	<5	<0.01	<10	<10	33	<10	79	2
8V3374RA/RJ	HL08-48	121120	29.52	31.40	1.88	0.02	0.5	1.82	6	140	<0.5	<5	4.52	<1	15	28	10	5.58	<1	0.24	<10	1.16	1623	<2	0.02	2	1508	13	3.79	<5	4	102	<5	<0.01	<10	<10	49	<10	93	3
8V3374RA/RJ	HL08-48	121121	31.40	33.40	2.00	0.01	0.3	1.72	7	138	<0.5	<5	4.55	<1	14	24	13	5.12	<1	0.21	<10	1.08	1566	<2	0.02	2	1443	11	3.21	<5	3	125	<5	<0.01	<10	10	42	<10	90	3
8V3374RA/RJ	HL08-48	121122	33.40	35.37	1.97	<0.01	0.4	1.78	7	156	<0.5	<5	4.16	<1	15	21	14	5.72	<1	0.24	<10	1.20	1641	<2	0.02	2	1530	11	3.30	<5	5	122	<5	<0.01	<10	11	45	<10	86	3
8V3374RA/RJ	HL08-48	121123	35.37	36.54	1.17	<0.01	0.5	1.41	17	146	<0.5	<5	5.27	<1	14	25	20	5.25	<1	0.24	<10	0.92	1680	<2	0.02	2	1413	25	3.45	<5	5	135	<5	<0.01	<10	<10	34	<10	107	2
8V3374RA/RJ	HL08-48	121124	36.54	37.84	1.30	0.01	0.4	1.51	7	159	<0.5	<5	4.86	<1	14	17	18	5.15	<1	0.27	<10	1.19	1820	<2	0.02	2	1380	9	2.98	<5	5	124	<5	<0.01	<10	<10	36	<10	99	2
8V3374RA/RJ	HL08-48	121125	Blank	Blank	<0.01	0.0	0.98	<5	261	<0.5	<5	0.59	<1	8	121	1	2.09	<1	0.49	<10	0.56	604	<2	0.07	7	729	3	0.91	<5	2	51	<5	0.13	<10	<10	41	<10	51	2	
8V3374RA/RJ	HL08-48	121126	37.84	39.14	1.30	0.02	0.5	0.66	19	128	<0.5	<5	5.45	<1	16	22	8	5.84	<1	0.27	<10	1.15	1936	<2	0.01	2	1491	21	4.47	<5	5	140	<5	<0.01	<10	11	21	<10	92	3
8V3374RA/RJ	HL08-48	121127	39.14	40.44	1.30	0.02	0.8	0.40	40	117	<0.5	<5	5.65	<1	12	38	10	4.71	<1	0.24	<10	0.95	1739	<2	0.01	2	1187	45	3.84	<5	5	217	<5	<0.01	<10	10	12	<10	75	2
8V3374RA/RJ	HL08-48	121128	40.44	41.59	1.15	0.03	2.5	0.30	52	101	<0.5	<5	9.31	<3	14	31	32	4.78	<1	0.19	<10	0.50	1898	9	0.01	3	1179	55	4.28	<5	4	469	<5	<0.01	<10	11	8	<10	275	2
8V3374RA/RJ	HL08-48	121129	41.59	42.81	1.22	0.04	1.3	0.62	31	106	<0.5	<5	4.32	<1	13	22	30	4.06	<1	0.19	<10	0.74	1448	3	0.01	3	1094	21	3.03	<5	4	110	<5	<0.01	<10	<10	13	<10	102	2
8V3374RA/RJ	HL08-48	121130	42.81	43.92	1.11	0.09	5.6	0.35	229	75	<0.5	<5	2.17	7	8	43	30	2.62	<1	0.20	<10	0.13	451	7	0.01	2	723	211	2.59	<5	1	68	<5	<0.01	<10	<10	7	<10	393	1
8V3374RA/RJ	HL08-48	121131	43.92	45.13	1.21	0.32	73.6	0.38	252	95	<0.5	<5	2.08	8	9	43	50	2.79	<1	0.19	<10	0.14	394	2	0.01	3	872	241	2.62	26	1	76	<5	<0.01	<10	<10	8	<10	496	2
8V3374RA/RJ	HL08-48	121132	45.13	45.68	0.55	<0.01	0.6	0.76	<5	190	<0.5	<5	2.03	<1	6	42	3	1.62	<1	0.20	17	0.54	332	<2	0.03	6	805	27	0.07	<5	2	75	<5	<0.01	<10	<10	19	<10	52	8
8V3374RA/RJ	HL08-48	121133	66.68	67.37	0.69	0.08	1.6	1.28	155	137	<0.5	<5	0.70	3	13	25	34	3.69	<1	0.25	<10	0.78	817	<2	0.01	3	1198	11	1.27	<5	2	33	<5	<0.01	<10	<10	32	<10	106	2
8V3374RA/RJ	HL08-48	121134	67.37	69.27	0.90	0.21	3.1	1.17	219	79	<0.5	<5	1.11	6	19	39	110	4.91	<1	0.21	<10	0.70	768	10	0.01	5	1050	138	3.22	<5	2	47	<5	<0.01	<10	<10	41	<10	344	2
8V3374RA/RJ	HL08-48	121135	69.27	71.27	2.00	0.12	1.4	1.51	98	125	<0.5	<5	1.39	2	14	18	56	4.05	<1	0.25	11	0.91	1065	3	0.01	3	1232	17	1.11	<5	2	59	<5	<0.01	<10	<10	38	<10	120	2
8V3374RA/RJ	HL08-48	121136	71.27	73.28	2.01	0.08	1.4	1.22	54	117	<0.5	<5	2.17	1	11	38	83	3.37	<1	0.24	<10	0.63	968	5	0.01	3	1129	17	0.95	<5	2	99	<5	<0.01	<10	<10	30	<10	140	2
8V3374RA/RJ	HL08-48	121137	73.28	75.28	2.00	0.10	1.3	1.72	24	125	<0.5	<5	3.27	1	13	14	72	4.19	<1	0.25	11	0.98	1550	4	0.02	3	1293	13	0.95	<5	3	149	<5	<0.01	<10	<10	43	<10	134	2
8V3374RA/RJ	HL08-48	121138	75.28	77.06	1.78	0.06	0.9	1.53	19	124	<0.5	<5	3.56	<1	11	15	57	3.92	<1	0.26	10	0.83	1362	2	0.02	2	1215	15	0.87	<5	2	160	<5	<0.01	<10	<10	41	<10	123	2
8V3374RA/RJ	HL08-48	121139	77.06	78.75	1.69	0.07	0.6	1.60	33	112	<0.5	<5	3.40	1	12	11	46	3.83	<1	0.23	10	0.90	1393	3	0.02	2	1165	11	0.47	<5	2	170	<5	<0.01	<10	<10	46	<10	106	2
8V3374RA/RJ	HL08-48	121140	78.75	80.30	1.55	0.06	0.8	1.60	37	139	<0.5	<5	4.02	1	12	12	45	3.89	<1	0.27	11	0.85	1598	3	0.02	3	1226	12	0.65	<5	2	200	<5	<0.01	<10	<10	40	<10	130	2
8V3374RA/RJ	HL08-48	121141	80.30	81.75	1.45	0.28	1.4	1.31	39	127	<0.5	<5	4.62	1	10	14	95	3.55	<1	0.25	<10	0.69	1695	9	0.01	2	1065	13	1.17	<5	2	202	<5	<0.01	<10	<10	31	<10	123	2
8V3374RA/RJ	HL08-48	121142	81.75	83.21	1.46	0.10	1.4	0.97	88	96	<0.5	<5	2.19	2	13	25	55	3.86	<1	0.25	<10	0.52	903	5	0.01	3	1114	16	2.52	<5	2	101	<5	<0.01	<10	<10	23	<10	122	2
8V3374RA/RJ	HL08-48	121143	83.21	84.27	1.06	0.06	1.4	0.69	127	88	<0.5	<5	0.86	3	12	33	26	3.78	<1	0.25	12	0.29	453	2	0.01	3	1039	17	3.11	<5	1	42	<5	<0.01	<10	<10	18	<10	96	2
8V3374RA/RJ	HL08-48	121144	84.27	85.55	1.28	0.22	3.1	0.52	221	65	<0.5	<5	0.45	5	13	43	14	4.26	<1	0.26	<10	0.16	251	2	0.01	4	1114	68	4.19	<5	1	28	<5	<0.01	<10	<10	12	<10	158	2
8V3374RA/RJ	HL08-48	121145	85.55	86.87	1.32	0.51	3.1	0.71	139	90	<0.5	<5	0.43	3	12	34	50	3.80	<1	0.25	<10	0.27	413	2	0.01	3	1102	71	3.03	<5	1	25	<5	<0.01	<10	<10	15	<10	176	2
8V3374RA/RJ	HL08-48	121146	86.87	88.55	1.68	0.19	5.0	0.79	400	107	<0.5	<5	0.41	13	12	26	51	3.24	<1	0.25	<10	0.31	498	4	0.01	3	1104	191	2.01	<5	1	24	<5	<0.01	<10	<10	17	<10	689	2
8V3374RA/RJ	HL08-48	121147	88.55	90.04	1.49	0.06	2.4	0.83	140	124	<0.5	<5	0.37	3	11	26	31	2.71	<1	0.29	<10	0.30	537	4	0.01	3	1099	29	1.27	<5	1	21	<5	<0.01	<10	<10	18	<10	130	1
8V3374RA/RJ	HL08-48	121148	90.04	91.09	1.05	0.10	5.3	0.49	481	89	<0.5	<5	0.50	16	9	52	55	2.25	<1	0.26	<10	0.12	286	5	0.01	4	992	355	2.81	<5	1	24	<5	<0.01	<10	<10	11</			

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:				S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Zr											
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm													Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm
8V3374RA/RJ	HL08-48	121190	152.87	154.27	1.40	0.32	4.6	2.22	206	174	<0.5	<5	0.58	7	26	17	229	6.63	<1	0.32	<10	1.53	1389	32	0.01	5	1563	45	1.71	<5	4	25	<5	<0.01	<10	<10	97	<10	322	3
8V3374RA/RJ	HL08-48	121191	154.27	155.77	1.50	0.26	4.7	2.25	178	158	<0.5	<5	0.45	5	26	16	234	6.95	<1	0.34	<10	1.57	1196	43	0.01	6	1555	44	2.36	<5	4	21	<5	<0.01	<10	<10	94	<10	277	3
8V3374RA/RJ	HL08-48	121192	155.77	157.27	1.50	0.23	4.1	2.50	99	142	<0.5	<5	0.43	3	26	15	184	6.89	<1	0.31	<10	1.69	1248	22	0.01	6	1591	43	1.54	<5	4	23	<5	<0.01	<10	<10	106	<10	288	3
8V3374RA/RJ	HL08-48	121193	157.27	159.27	2.00	0.52	4.4	2.49	257	168	<0.5	<5	0.51	7	27	15	359	6.89	<1	0.31	<10	1.69	1337	32	0.01	6	1620	34	1.55	<5	3	20	<5	<0.01	<10	<11	97	<10	303	3
8V3374RA/RJ	HL08-48	121194	159.27	160.37	1.00	0.16	4.8	1.63	174	150	<0.5	<5	0.60	5	25	15	296	6.04	<1	0.38	<10	1.00	887	37	0.01	4	1663	34	3.00	<5	3	27	<5	<0.01	<10	<11	97	<10	241	3
8V3374RA/RJ	HL08-48	121195	160.37	161.82	1.45	0.20	5.7	1.41	166	126	<0.5	<5	0.68	4	25	9	359	6.31	<1	0.35	<10	1.11	1108	43	0.01	5	1460	45	3.25	<5	3	35	<5	<0.01	<10	<11	55	<10	284	3
8V3374RA/RJ	HL08-48	121196	161.82	163.32	1.50	0.21	4.0	2.38	369	134	<0.5	<5	2.13	9	25	9	235	6.38	<1	0.35	<10	1.66	1908	21	0.01	4	1509	39	1.66	<5	4	116	<5	<0.01	<10	<11	82	<10	250	3
8V3374RA/RJ	HL08-48	121197	163.32	164.68	1.36	0.48	7.4	1.83	533	122	<0.5	<5	0.49	13	31	8	309	6.98	<1	0.40	<10	0.89	993	34	0.01	5	1562	61	3.64	<5	4	27	<5	<0.01	<10	<11	63	<10	330	3
8V3374RA/RJ	HL08-48	121198	164.68	166.68	2.00	0.46	12.8	1.50	458	137	<0.5	<5	0.82	11	20	13	262	5.36	<1	0.34	<10	0.62	1002	26	0.01	4	1440	62	2.15	<5	3	45	<5	<0.01	<10	<10	45	<10	421	2
8V3374RA/RJ	HL08-48	121199	166.68	168.18	1.50	0.13	5.9	1.57	232	116	<0.5	<5	2.14	5	21	13	165	5.63	<1	0.34	<10	0.70	1250	27	0.01	4	1484	31	2.41	<5	3	89	<5	<0.01	<10	<10	62	<10	185	3
8V3374RA/RJ	HL08-48	121200	Std	PM922		6.34	3.3	1.59	816	181	<0.5	<5	9.65	18	54	80	505	6.55	14	0.20	13	0.37	1014	144	0.04	82	1134	97	2.57	<5	4	125	<5	0.14	<10	<10	47	54	100	19
8V3374RA/RJ	HL08-48	121201	168.18	169.65	1.47	0.34	4.8	1.68	344	141	<0.5	<5	4.29	8	22	21	208	5.89	<1	0.37	<10	0.66	1587	28	0.02	5	1524	46	2.40	<5	5	122	<5	<0.01	<10	<10	63	<10	204	2
8V3374RA/RJ	HL08-48	121202	169.65	171.15	1.50	0.39	4.0	1.21	597	141	<0.5	<5	4.33	14	22	15	181	5.70	<1	0.38	<10	0.62	1550	94	0.02	5	1540	43	3.59	<5	4	128	<5	<0.01	<10	<10	44	<10	255	2
8V3374RA/RJ	HL08-48	121203	171.15	172.65	1.50	0.46	3.6	1.24	241	160	<0.5	<5	4.45	5	22	41	164	5.89	<1	0.43	<10	0.42	1440	25	0.02	6	1261	40	3.25	<5	3	133	<5	0.03	<10	<10	44	<10	181	2
8V3374RA/RJ	HL08-48	121204	172.65	174.15	1.50	0.49	4.2	1.39	271	126	<0.5	<5	3.59	6	25	17	234	6.48	<1	0.40	<10	0.43	1212	60	0.01	7	1744	45	4.11	<5	4	127	<5	<0.01	<10	<10	47	<10	216	3
8V3374RA/RJ	HL08-48	121205	174.15	175.65	1.50	0.22	3.3	2.03	73	134	<0.5	<5	4.91	2	25	14	304	6.48	<1	0.39	<10	0.74	1608	38	0.01	5	1804	34	1.55	<5	5	156	<5	0.01	<10	<10	74	<10	214	3
8V3374RA/RJ	HL08-48	121206	175.65	177.13	1.48	0.27	2.5	2.17	66	134	<0.5	<5	4.62	2	24	9	202	6.57	<1	0.36	<10	0.88	1456	28	0.01	6	1861	40	1.52	<5	5	155	<5	0.01	<10	<10	71	<10	232	3
8V3374RA/RJ	HL08-48	121207	177.13	178.66	1.53	0.94	3.5	1.66	207	137	<0.5	<5	4.37	5	22	12	205	5.47	<1	0.39	<10	0.60	1182	77	0.01	8	1712	83	1.86	<5	4	157	<5	<0.01	<10	<10	66	<10	123	2
8V3374RA/RJ	HL08-48	121208	178.66	180.14	1.48	0.20	3.7	1.94	445	137	<0.5	<5	4.06	11	21	8	169	6.04	<1	0.37	<10	0.77	1623	22	0.01	7	1768	29	1.73	<5	4	137	<5	<0.01	<10	<10	56	<10	323	3
8V3374RA/RJ	HL08-48	121209	180.14	181.95	1.81	0.33	3.7	1.78	562	131	<0.5	<5	3.97	13	25	10	164	6.04	<1	0.38	<10	0.70	1504	31	0.01	8	1802	41	2.25	<5	4	145	<5	<0.01	<10	<10	64	<10	298	3
8V3374RA/RJ	HL08-48	121210	181.95	183.64	1.69	0.28	3.6	1.72	291	116	<0.5	<5	4.99	6	22	9	165	6.69	<1	0.38	<10	0.73	1546	18	0.01	6	1665	36	2.56	<5	4	139	<5	<0.01	<10	<10	65	<10	175	3
8V3374RA/RJ	HL08-48	121211	183.64	185.44	1.80	0.40	6.1	2.11	273	134	<0.5	<5	4.43	11	20	13	192	6.18	<1	0.36	<10	0.81	1776	11	0.01	6	1394	651	1.65	<5	3	155	<5	<0.01	<10	<13	69	13	746	2
8V3374RA/RJ	HL08-48	121212	185.44	187.20	1.76	0.44	4.8	1.84	851	129	<0.5	<5	7.38	22	23	9	148	5.78	<1	0.37	<10	0.67	2558	14	0.01	6	1425	100	1.66	<5	4	235	<5	<0.01	<10	<15	90	10	616	2
8V3374RA/RJ	HL08-48	121213	187.20	189.25	2.05	0.33	9.0	1.78	517	141	<0.5	<5	4.75	14	24	17	158	5.69	<1	0.40	<10	0.70	1750	7	0.01	6	1483	114	2.04	<5	4	146	<5	<0.01	<10	<10	62	<10	365	2
8V3374RA/RJ	HL08-48	121214	189.25	191.12	1.87	0.35	5.7	1.63	836	153	<0.5	<5	4.76	22	26	10	178	5.87	<1	0.42	<10	0.67	1942	8	0.01	8	1629	49	2.14	<5	5	170	<5	<0.01	<10	<15	70	<10	311	2
8V3374RA/RJ	HL08-48	121215	191.12	192.73	1.61	0.25	5.8	1.03	322	130	<0.5	<5	3.85	16	19	17	75	5.15	<1	0.37	<10	0.43	1362	3	0.01	4	1374	84	3.74	<5	3	138	<5	<0.01	<10	<10	34	<10	496	2
8V3374RA/RJ	HL08-48	121216	192.73	194.23	1.50	0.60	3.6	0.97	955	118	<0.5	<5	5.52	23	21	12	66	5.23	<1	0.40	<10	0.42	1483	3	0.01	4	1466	56	4.15	<5	3	225	<5	<0.01	<10	<10	48	<10	180	2
8V3374RA/RJ	HL08-48	121217	194.23	195.73	1.50	0.65	2.0	0.99	963	108	<0.5	<5	5.73	22	19	11	26	5.14	<1	0.43	<10	0.48	1704	2	0.01	3	1441	49	4.39	<5	3	269	<5	0.01	<10	<10	35	<10	106	2
8V3374RA/RJ	HL08-48	121218	195.73	196.25	0.52	0.29	2.1	0.80	1233	111	<0.5	<5	6.32	28	16	8	48	4.63	<1	0.41	<10	0.48	1971	9	0.01	2	1439	51	3.51	<5	3	280	<5	<0.01	<10	<13	22	<10	160	2
8V3374RA/RJ	HL08-48	121219	196.25	198.70	2.45	0.32	10.9	0.75	284	88	<0.5	<5	9.94	10																										

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm	
8V3374RA/RJ	HL08-50	121251	4.63	6.04	4.41	0.02	0.5	1.53	18	92	<0.5	<5	5.40	<1	14	17	17	5.13	<1	0.20	<10	1.18	1742	<2	0.02	1	1421	18	2.77	<5	3	182	<5	<0.01	<10	<10	32	<10	102	2	
8V3374RA/RJ	HL08-50	121252	6.04	7.93	1.89	0.01	0.4	1.74	17	127	<0.5	<5	3.44	<1	12	21	13	5.68	<1	0.20	<10	1.13	1585	<2	0.04	2	1651	18	3.37	<5	3	62	<5	<0.01	<10	<10	34	<10	103	3	
8V3374RA/RJ	HL08-50	121253	7.93	9.93	2.00	0.01	0.4	2.16	9	137	<0.5	<5	3.73	<1	12	15	13	5.24	<1	0.21	<10	1.66	1871	<2	0.03	1	1482	19	1.96	<5	4	59	<5	0.01	<10	<10	59	<10	133	2	
8V3374RA/RJ	HL08-50	121254	9.93	11.93	2.00	0.02	0.2	1.76	16	125	<0.5	<5	5.19	<1	12	18	15	4.96	<1	0.19	<10	1.20	1647	<2	0.02	1	1467	10	2.36	<5	3	75	<5	0.01	<10	<10	39	<10	108	2	
8V3374RA/RJ	HL08-50	121255	11.93	13.29	1.36	0.01	0.2	1.89	9	109	<0.5	<5	4.75	<1	11	15	13	4.89	<1	0.16	<10	1.21	1574	<2	0.02	1	1462	10	1.90	<5	3	68	<5	0.01	<10	<10	35	<10	98	2	
8V3374RA/RJ	HL08-50	121256	13.29	14.60	1.31	0.01	0.5	1.74	16	123	<0.5	<5	5.03	<1	15	20	41	5.09	<1	0.20	<10	1.11	1588	<2	0.01	2	1413	20	2.05	<5	3	99	<5	<0.01	<10	<10	40	<10	82	2	
8V3374RA/RJ	HL08-50	121257	18.11	20.11	2.00	0.02	0.5	1.58	21	108	<0.5	<5	3.85	<1	16	23	23	5.92	<1	0.20	<10	1.00	1190	<2	0.01	2	1583	25	3.77	<5	3	83	<5	<0.01	<10	<10	27	<10	82	3	
8V3374RA/RJ	HL08-50	121258	20.11	22.11	2.00	0.02	0.3	1.76	16	114	<0.5	<5	5.11	<1	13	25	13	5.57	<1	0.17	<10	1.17	1488	<2	0.01	2	1587	8	3.08	<5	3	114	<5	0.01	<10	<10	33	<10	94	2	
8V3374RA/RJ	HL08-50	121259	22.11	24.11	2.00	0.02	0.3	2.09	16	168	<0.5	<5	2.41	<1	14	18	9	5.72	<1	0.18	<10	1.44	1398	<2	0.02	1	1665	26	2.03	<5	4	48	<5	<0.01	<10	<10	53	<10	165	2	
8V3374RA/RJ	HL08-50	121260	24.11	26.11	2.00	0.01	0.3	1.74	29	69	<0.5	<5	4.36	<1	13	24	9	5.58	<1	0.20	<10	1.18	1528	<2	0.02	2	1617	14	3.15	<5	3	99	<5	0.01	<10	<10	42	<10	83	2	
8V3374RA/RJ	HL08-50	121261	26.11	28.11	2.00	0.01	<0.1	1.99	6	110	<0.5	<5	4.20	<1	15	17	14	5.20	<1	0.19	<10	1.30	1681	<2	0.01	2	1667	16	3.06	<5	4	119	<5	0.04	<10	<10	49	<10	105	3	
8V3374RA/RJ	HL08-50	121262	28.11	29.54	1.43	0.01	<0.1	1.93	12	100	<0.5	<5	5.29	<1	16	19	16	5.71	<1	0.17	<10	1.31	1928	<2	0.01	2	1636	15	3.69	<5	3	154	<5	0.04	<10	<10	41	<10	88	3	
8V3374RA/RJ	HL08-50	121262A	29.54	31.24	1.70	0.02	<0.1	2.18	5	130	<0.5	<5	3.33	<1	15	16	29	5.44	<1	0.18	<10	1.47	1721	<2	0.02	2	1709	12	2.65	<5	4	97	<5	0.07	<10	<10	48	<10	84	3	
8V3395RA/RJ	HL08-50	121263	31.24	33.24	2.00	0.02	<0.1	1.71	6	102	<0.5	<5	3.61	<1	13	38	24	4.66	<1	0.15	<10	1.24	1531	<2	0.01	9	1431	12	2.36	<5	3	115	<5	0.03	<10	<10	38	<10	69	2	
8V3395RA/RJ	HL08-50	121264	33.24	35.24	2.00	0.01	<0.1	1.81	7	110	<0.5	<5	3.23	<1	16	24	10	5.34	<1	0.19	<10	1.37	1507	<2	0.01	10	1583	29	3.14	<5	3	101	<5	0.02	<10	<10	45	<10	101	3	
8V3395RA/RJ	HL08-50	121265	35.24	37.24	2.00	0.02	1.0	1.27	36	129	<0.5	<5	4.74	<1	23	13	33	87	4.27	<1	0.17	<10	0.86	1566	<2	0.01	4	1381	177	2.90	<5	2	118	<5	<0.01	<10	<10	29	<10	270	2
8V3395RA/RJ	HL08-50	121266	37.24	39.24	2.00	0.03	0.6	0.74	50	105	<0.5	<5	4.22	<1	10	43	42	3.20	<1	0.17	<10	0.44	1256	<2	0.01	5	998	139	2.49	<5	1	91	<5	<0.01	<10	<10	17	<10	322	1	
8V3395RA/RJ	HL08-50	121267	39.24	41.24	2.00	0.09	3.5	0.41	155	82	<0.5	<5	4.41	<1	6	10	44	90	3.46	<1	0.14	<10	0.21	1032	<3	0.01	4	937	145	3.42	<5	1	118	<5	<0.01	<10	<10	9	<10	537	1
8V3395RA/RJ	HL08-50	121268	41.24	42.71	1.47	0.07	13.1	0.56	150	93	<0.5	<5	7.66	<1	11	12	48	88	4.23	<1	0.17	<10	0.34	1629	<2	0.01	5	1049	538	3.70	<5	2	391	<5	<0.01	<10	<10	11	<10	1206	2
8V3395RA/RJ	HL08-50	121269	42.71	44.71	2.00	0.02	0.2	1.83	27	96	<0.5	<5	3.80	<1	16	15	33	4.82	<1	0.19	<10	1.21	1630	<4	0.01	3	1426	12	1.42	<5	3	129	<5	<0.01	<10	<10	39	<10	97	2	
8V3395RA/RJ	HL08-50	121270	44.71	46.51	1.80	0.03	0.2	1.45	27	92	<0.5	<5	4.33	<1	13	25	40	4.08	<1	0.19	<10	0.78	1156	<7	0.01	3	1409	32	1.48	<5	2	245	<5	<0.01	<10	<10	33	<10	67	2	
8V3395RA/RJ	HL08-50	121271	51.06	52.65	1.59	0.01	<0.1	1.75	34	114	<0.5	<5	5.32	<1	16	25	79	4.41	<1	0.13	<10	0.98	1955	<2	0.07	5	1190	10	0.56	<5	4	136	<5	0.02	<10	<10	66	<10	67	2	
8V3395RA/RJ	HL08-50	121272	52.65	54.65	2.00	0.06	<0.1	1.77	15	102	<0.5	<5	4.42	<1	13	19	41	4.12	<1	0.17	<10	1.05	1695	<6	0.03	4	1320	16	0.57	<5	3	141	<5	0.01	<10	<10	52	<10	83	2	
8V3395RA/RJ	HL08-50	121273	54.65	56.65	2.00	0.05	0.5	1.61	39	101	<0.5	<5	3.42	<1	13	20	64	4.08	<1	0.18	<10	1.01	1213	<8	0.01	3	1412	17	1.24	<5	2	162	<5	<0.01	<10	<10	35	<10	109	2	
8V3395RA/RJ	HL08-50	121274	56.65	58.66	2.01	0.04	0.5	1.75	48	105	<0.5	<5	1.92	<1	15	14	40	4.57	<1	0.20	<10	1.04	1181	<4	0.01	3	1504	15	1.11	<5	2	79	<5	<0.01	<10	<10	43	<10	101	2	
8V3633RA/RJ	HL08-50	122618	58.66	60.66	2.00	0.02	0.4	1.75	33	88	<0.5	<5	5.30	<1	11	23	29	3.91	<1	0.18	<10	1.00	1397	<2	0.03	2	1150	24	0.40	<5	8	195	<5	0.01	<10	<10	51	<10	81	2	
8V3633RA/RJ	HL08-50	122619	60.66	62.66	2.00	0.03	1.1	1.50	87	80	<0.5	<5	4.78	<1	2	11	8	6.2	4.33	<1	0.15	<10	0.97	1500	<2	0.02	1	1254	26	1.58	<5	2	167	<5	<0.01	<10	<10	33	<10	175	2
8V3633RA/RJ	HL08-50	122620	62.66	64.00	1.34	0.03	0.8	1.68	22	135	<0.5	<5	4.88	<1	12	14	56	3.98	<1	0.25	<10	0.91	1558	<2	0.02	1	1275	25	0.94	<5	8	2	158	<5	0.01	<10	<10	32	<10	118	2
8V3633RA/RJ	HL08-50	122621	64.00	65.05	1.05	0.03	0.9	1.64	47	127	<0.5	<5	3.97	<1	12	15	45	3.98	<1	0.24	<10	0.91	1383	<2	0.02	2	1255	22	1.11	<5	9	2	148	<5	<0.01	<10	<10	35	<10	108	2
8V3395RA/RJ	HL08-50	121275	Std	PM952			5.23	2.6	1.45	768	140	<0.5	<4	8.77	16	53	75	4.77	6.07	13	0.18	12	37																		

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:				S				Sb				Sc				Sr				Th				Ti				U				V				W				Zn				Zr			
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Ti ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm																					
8V3395RA/RJ	HL08-51	121313	26.10	28.10	2.00	0.02	2.3	1.95	111	82	<0.5	<5	1.16	3	28	20	65	6.18	<1	0.17	<10	1.54	1473	<2	0.02	5	1717	81	2.10	<5	4	63	<5	<0.01	<10	<10	66	<10	205	3																					
8V3395RA/RJ	HL08-51	121314	28.10	30.10	2.00	0.01	0.4	1.87	85	91	<0.5	<5	1.04	1	27	14	39	6.14	<1	0.15	<10	1.41	1324	<2	0.02	5	1771	25	2.65	<5	4	52	<5	0.01	<10	<10	70	<10	21	125	3																				
8V3395RA/RJ	HL08-51	121315	30.10	32.10	2.00	0.01	0.3	1.95	78	81	<0.5	<5	0.99	1	25	15	43	5.85	<1	0.15	<10	1.41	1264	<2	0.02	4	1726	14	1.99	<5	4	45	<5	0.01	<10	<10	69	<10	102	2																					
8V3395RA/RJ	HL08-51	121316	32.10	34.10	2.00	0.04	1.5	1.70	185	99	<0.5	<5	0.56	3	27	16	54	6.02	<1	0.20	<10	1.13	986	<2	0.02	4	1720	16	2.86	<5	3	26	<5	<0.01	<10	<10	52	<10	95	3																					
8V3395RA/RJ	HL08-51	121317	34.10	36.10	2.00	0.08	2.2	1.90	176	97	<0.5	<5	0.61	3	28	16	50	6.28	<1	0.20	<10	1.38	1150	<2	0.01	5	1831	15	2.84	<5	3	32	<5	<0.01	<10	<10	54	<10	105	3																					
8V3395RA/RJ	HL08-51	121318	36.10	38.10	2.00	0.03	0.8	1.85	146	96	<0.5	<5	0.81	2	28	17	15	6.43	<1	0.19	<10	1.46	1165	<2	0.01	4	1744	17	3.29	<5	3	47	<5	0.01	<10	<10	56	<10	115	3																					
8V3395RA/RJ	HL08-51	121319	38.10	40.10	2.00	0.02	0.8	1.73	163	69	<0.5	<5	0.72	3	28	14	23	5.97	<1	0.15	<10	1.50	1132	<2	0.02	4	1749	15	2.80	<5	3	39	<5	<0.01	<10	<10	59	<10	131	2																					
8V3395RA/RJ	HL08-51	121320	40.10	42.10	2.00	0.02	0.9	1.86	103	69	<0.5	<5	0.62	1	27	17	17	5.92	<1	0.14	<10	1.58	1230	<2	0.02	7	1785	13	2.40	<5	4	27	<5	<0.01	<10	<10	64	<10	13	104	2																				
8V3395RA/RJ	HL08-51	121321	42.10	44.10	2.00	0.02	0.2	1.95	72	61	<0.5	<5	1.06	1	27	14	21	5.74	<1	0.14	<10	1.56	1395	<2	0.02	4	1727	11	1.87	<5	4	52	<5	<0.01	<10	<10	66	<10	17	91	2																				
8V3395RA/RJ	HL08-51	121322	44.10	46.10	2.00	0.03	1.0	1.99	136	60	<0.5	<5	0.99	3	28	11	55	6.21	<1	0.15	<10	1.54	1535	<2	0.01	4	1763	41	2.08	<5	4	48	<5	<0.01	<10	<10	59	<10	141	2																					
8V3395RA/RJ	HL08-51	121323	46.10	47.56	1.46	0.06	2.2	1.71	200	78	<0.5	<5	0.47	6	26	19	55	5.84	<1	0.16	<10	1.13	1327	<2	0.01	4	1484	202	2.51	<5	3	20	<5	<0.01	<10	<10	54	<10	325	2																					
8V3395RA/RJ	HL08-51	121324	47.56	49.74	2.18	0.08	2.1	1.89	294	75	<0.5	<5	0.42	8	26	11	58	5.91	<1	0.19	<10	1.37	1376	<2	0.01	5	1658	89	2.49	<5	3	18	<5	<0.01	<10	<10	55	<10	471	3																					
8V3395RA/RJ	HL08-51	121325	Blank	Blank		<0.01	<0.1	0.90	<5	242	<0.5	<5	0.46	<1	9	90	<1	2.24	<1	0.45	<10	0.62	579	<2	0.05	5	860	2	0.01	<5	2	41	<5	0.14	<10	<10	41	<10	50	2																					
8V3395RA/RJ	HL08-51	121326	49.74	50.74	1.00	0.62	17.5	0.34	1200	23	<0.5	<12	0.28	147	10	55	229	14.34	4	0.11	<10	0.19	294	<2	0.01	2	664	3164	>5.00	<5	1	12	<5	<0.01	<10	26	15	264	14100	6																					
8V3395RA/RJ	HL08-51	121327	50.74	51.74	1.00	0.90	88.6	0.26	549	38	<0.5	<5	0.87	65	8	69	100	8.26	3	0.10	<10	0.15	254	<2	0.01	3	606	1867	>5.00	7	<1	22	<5	<0.01	<10	<10	9	109	6875	3																					
8V3395RA/RJ	HL08-51	121328	51.74	52.74	1.00	3.17	165.0	0.16	547	28	<0.5	<5	0.44	61	5	77	117	6.41	4	0.07	<10	0.08	160	<2	0.01	3	351	2966	>5.00	44	<1	16	<5	<0.01	<10	<10	5	99	6553	3																					
8V3395RA/RJ	HL08-51	121329	52.74	53.74	1.00	0.95	85.1	0.58	278	36	<0.5	<5	0.85	32	11	96	100	5.70	2	0.08	<10	0.42	456	<7	0.01	4	689	5089	>5.00	13	1	51	<5	<0.01	<10	<10	19	53	3524	3																					
8V3395RA/RJ	HL08-51	121330	53.74	54.74	1.00	0.08	2.4	0.32	150	79	<0.5	<5	<0.01	11	15	66	20	0.34	<1	0.09	<10	0.24	778	<2	0.01	2	893	235	3.18	10	2	67	<5	<0.01	<10	<10	34	<10	736	2																					
8V3395RA/RJ	HL08-51	121331	54.74	55.74	1.00	0.30	10.6	<0.01	218	52	<0.5	<5	<0.01	22	13	68	75	<0.01	<1	0.05	<10	0.08	552	<4	0.01	2	697	918	>5.00	15	1	71	<5	<0.01	<10	<10	19	28	2550	2																					
8V3395RA/RJ	HL08-51	121332	55.74	56.74	1.00	0.17	4.5	1.34	223	51	<0.5	<5	4.16	16	18	24	49	6.23	<1	0.13	<10	0.95	1352	<3	0.01	1	1097	618	>5.00	14	2	214	<5	0.01	<10	<10	43	20	1666	3																					
8V3395RA/RJ	HL08-51	121333	56.74	57.74	1.00	0.09	1.1	1.12	169	62	<0.5	<5	1.91	4	18	49	19	4.53	<1	0.13	<10	0.79	978	<2	0.01	2	1105	128	3.40	9	2	66	<5	<0.01	<10	<10	38	<10	281	2																					
8V3395RA/RJ	HL08-51	121334	57.74	59.24	1.50	0.04	1.5	1.56	147	67	<0.5	<5	2.42	4	23	26	43	5.13	<1	0.15	<10	1.16	1335	<2	0.01	2	1207	159	3.42	10	3	90	<5	0.03	<10	<10	52	<10	405	3																					
8V3395RA/RJ	HL08-51	121335	59.24	61.11	1.87	0.05	0.4	1.53	145	59	<0.5	<5	3.34	3	20	17	28	4.97	<1	0.13	<10	1.08	1462	<2	0.01	1	1148	83	3.20	9	3	122	<5	0.06	<10	<10	53	<10	200	3																					
8V3395RA/RJ	HL08-51	121336	61.11	62.11	1.00	0.38	13.4	0.95	309	51	<0.5	<5	8	6.71	101	19	23	121	7.28	2	0.12	<10	0.70	2100	<2	0.01	<1	952	7234	>5.00	17	2	326	<5	0.04	<10	13	36	149	15100	4																				
8V3395RA/RJ	HL08-51	121337	62.11	63.13	1.02	0.04	0.6	1.79	124	56	<0.7	<5	4.05	4	20	12	28	5.10	<1	0.12	<10	1.33	1777	<2	0.01	1	1250	229	2.83	10	3	145	<5	0.09	<10	<10	52	<10	462	3																					
8V3395RA/RJ	HL08-51	121338	63.13	65.13	2.00	0.02	<0.1	2.24	55	60	<0.6	<5	2.89	<1	20	14	25	5.06	<1	0.12	<10	1.61	1488	<2	0.01	1	1071	47	1.55	9	4	105	<5	0.08	<10	<10	65	<10	110	2																					
8V3395RA/RJ	HL08-51	121339	65.13	67.13	2.00	0.03	<0.1	1.90	45	60	<0.5	<5	3.18	<1	18	12	48	4.68	<1	0.12	<10	1.23	1318	<2	0.01	1	1088	33	1.69	8	4	126	<5	0.06	<10	<10	62	<10	106	3																					
8V3395RA/RJ	HL08-51	121340	67.13	69.13	2.00	0.02	0.3	1.98	56	68	<0.5	<5	3.43	1	19	15	57	5.51	<1	0.15	<10	1.29	1301	<2	0.01	1	1190	39	2.31	9	4	111	<5	0.05	<10	<10	64	<10	132	3																					
8V3395RA/RJ	HL08-51	121341	69.13	70.47	1.34	0.03	0.5	2.12	63	56	<0.7	<5	2.20	1	19	10	76	4.96	<1	0.12	<10	1.48	1207	<2	0.01	1	1131	49	1.47	9	4	77	<5	0.08	<10	<10	66	<10	125	3																					
8V3395RA/RJ	HL08-51	121342	70.47	71.95	1.48	0.08	0.8	1.53	127	59	<0.5	<5	1.56	2	18	18	40	4.73	<1	0.14	<10	0.96	821	&																																					

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																												
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm	
8V3395RA/RJ	HLO8-53	121383	34.83	36.83	2.00	0.02	0.6	2.30	54	88	<0.5	<5	4.69	<1	25	9	88	6.24	<1	0.32	10	1.36	2771	<2	0.01	3	1726	61	1.23	8	4	172	<5	0.02	<10	12	66	<10	126	3	
8V3395RA/RJ	HLO8-53	121384	36.83	38.83	2.00	0.03	0.2	<0.01	28	86	0.5	<5	<0.01	<1	23	8	29	<0.01	<1	0.06	11	0.04	2244	<2	<0.01	2	1377	147	0.83	9	4	129	<5	0.08	<10	<10	58	<10	80	3	
8V3395RA/RJ	HLO8-53	121385	38.83	40.83	2.00	0.01	<0.1	1.71	28	119	0.8	<5	4.24	<1	24	10	14	4.44	<1	0.35	11	0.78	2023	<2	0.01	3	1292	24	0.92	9	4	148	<5	0.11	<10	<10	55	<10	55	4	
8V3395RA/RJ	HLO8-53	121386	40.83	42.83	2.00	0.01	0.2	1.64	44	129	<0.5	<5	4.20	2	26	12	30	4.52	<1	0.28	10	0.94	2346	<2	0.01	3	1292	158	1.02	8	4	103	<5	0.06	<10	<10	56	<10	267	2	
8V3395RA/RJ	HLO8-53	121387	42.83	44.83	2.00	0.02	0.3	1.58	57	89	<0.5	<5	4.08	1	28	6	78	4.79	<1	0.26	<10	0.97	2448	<2	0.01	4	1437	60	1.13	8	4	129	<5	0.02	<10	<10	54	<10	137	2	
8V3395RA/RJ	HLO8-53	121388	44.83	46.83	2.00	0.04	<0.1	0.99	35	94	<0.5	<5	8.45	1	14	13	45	2.99	<1	0.24	<10	0.45	2661	<2	0.01	2	961	94	0.75	5	2	303	<5	0.01	<10	<10	25	<10	145	2	
8V3395RA/RJ	HLO8-53	121389	46.83	48.83	2.00	0.02	<0.1	1.33	21	65	<0.5	<5	4.22	<1	16	7	48	3.54	<1	0.24	<10	0.90	2117	<2	0.01	2	1275	43	0.68	7	2	124	<5	<0.01	<10	<10	30	<10	65	2	
8V3395RA/RJ	HLO8-53	121390	48.83	50.83	2.00	0.01	<0.1	<0.01	23	79	<0.5	<5	<0.01	<1	15	6	30	<0.01	<1	0.06	<10	0.04	2083	<2	<0.01	2	1173	45	0.69	6	2	125	<5	<0.01	<10	<10	36	<10	63	2	
8V3395RA/RJ	HLO8-53	121391	50.83	52.16	1.33	0.01	<0.1	0.88	21	91	<0.5	<5	3.37	<1	16	3	22	4.30	<1	0.20	<10	0.99	1743	<2	0.01	2	1216	40	0.57	5	3	139	<5	<0.01	<10	<10	30	<10	70	2	
8V3395RA/RJ	HLO8-53	121392	52.16	54.16	2.00	0.04	<0.1	0.19	44	63	<0.5	<5	3.42	2	6	21	17	2.20	<1	0.16	<10	0.44	1547	2	0.01	1	636	74	1.00	<5	2	143	<5	<0.01	<10	<10	7	<10	164	2	
8V3497RA/RJ	HLO8-53	121393	54.16	55.93	1.77	0.05	4.0	0.27	56	123	<0.5	<5	4.61	1	7	40	16	2.87	<1	0.22	<10	0.58	1981	<2	0.01	2	922	53	1.11	<5	2	146	<5	<0.01	<10	<10	15	<10	153	2	
8V3497RA/RJ	HLO8-53	121394	55.93	57.89	1.96	0.02	0.7	0.43	45	164	<0.5	<5	3.79	1	8	36	12	2.90	<1	0.20	<10	0.39	1433	2	0.01	2	1033	37	1.61	<5	2	95	<5	<0.01	<10	<10	21	<10	137	3	
8V3497RA/RJ	HLO8-53	121395	57.89	59.90	2.01	0.04	0.6	0.28	56	129	<0.5	<5	6.21	1	7	35	12	2.51	<1	0.23	<10	0.31	1702	2	0.01	2	910	27	1.61	<5	2	143	<5	<0.01	<10	<10	10	<10	123	2	
8V3497RA/RJ	HLO8-53	121396	59.90	61.90	2.00	0.03	<0.1	0.65	71	99	<0.5	<5	2.86	1	8	32	9	2.86	<1	0.23	<10	0.45	1256	3	0.02	2	1023	24	1.27	<5	2	86	<5	<0.01	<10	<10	29	<10	96	3	
8V3497RA/RJ	HLO8-53	121397	61.90	63.90	2.00	0.05	0.5	0.50	56	86	<0.5	<5	3.18	1	8	42	10	3.03	<1	0.22	<10	0.43	1246	2	0.01	2	950	32	1.73	<5	2	81	<5	<0.01	<10	<10	23	<10	92	3	
8V3497RA/RJ	HLO8-53	121398	63.90	65.90	2.00	0.08	0.2	0.33	44	106	<0.5	<5	3.67	1	7	40	9	3.13	<1	0.22	<10	0.51	1455	2	0.01	2	922	31	1.93	<5	2	126	<5	<0.01	<10	<10	14	<10	70	3	
8V3497RA/RJ	HLO8-53	121399	65.90	67.89	1.99	0.05	<0.1	0.82	39	98	<0.5	<5	3.03	<1	8	46	9	3.17	<1	0.20	<10	0.69	1441	2	0.02	2	945	16	1.40	<5	2	87	<5	<0.01	<10	<10	31	<10	73	3	
8V3497RA/RJ	HLO8-53	121400	Std	PM1116	0.13	793.2	0.48	593	146	<0.5	104	0.51	19	6	18	7952	2.26	7	0.13	<10	0.51	273	589	0.03	5	754	976	1.27	1748	1	72	<5	0.03	<10	<10	12	<10	976	2		
8V3497RA/RJ	HLO8-53	121401	67.89	69.89	2.00	0.03	1.5	0.90	41	80	<0.5	<5	3.06	<1	8	40	19	3.39	<1	0.20	<10	0.71	1534	3	0.02	2	1024	21	1.71	<5	2	94	<5	<0.01	<10	<10	28	<10	61	3	
8V3497RA/RJ	HLO8-53	121402	69.89	71.89	2.00	0.33	0.9	0.67	51	89	<0.5	<5	4.48	1	7	43	10	2.91	<1	0.20	<10	0.52	1691	3	0.01	1	860	31	1.90	<5	1	121	<5	<0.01	<10	<10	20	<10	100	3	
8V3497RA/RJ	HLO8-53	121403	71.89	73.89	2.00	0.11	0.4	0.50	63	77	<0.5	<5	3.98	1	6	42	7	2.75	<1	0.21	<10	0.43	1537	3	0.01	2	846	16	2.19	<5	1	124	<5	<0.01	<10	<10	14	<10	47	3	
8V3497RA/RJ	HLO8-53	121404	73.89	75.62	1.73	0.05	0.2	0.44	71	83	<0.5	<5	3.12	1	7	45	5	2.89	<1	0.21	<10	0.39	1198	2	0.01	2	838	12	2.51	<5	1	99	<5	<0.01	<10	<10	13	<10	49	3	
8V3497RA/RJ	HLO8-53	121405	75.62	77.62	2.00	0.12	0.2	0.46	96	98	<0.5	<5	3.72	1	8	30	4	3.22	<1	0.23	<10	0.55	1656	3	0.01	1	958	18	2.53	<5	1	131	<5	<0.01	<10	<10	13	<10	52	3	
8V3497RA/RJ	HLO8-53	121406	77.62	79.62	2.00	0.04	0.3	1.09	82	91	<0.5	<5	3.84	1	13	27	6	4.11	<1	0.22	<10	0.95	2196	<2	0.01	2	1389	24	2.58	<5	2	122	<5	<0.01	<10	<10	38	<10	61	3	
8V3497RA/RJ	HLO8-53	121407	79.62	81.62	2.00	0.06	0.8	1.79	134	72	<0.5	6	5.49	4	19	13	44	5.56	<1	0.23	<10	1.51	3438	<2	0.01	3	1733	86	2.46	<5	2	196	<5	<0.01	<10	22	54	<10	348	2	
8V3497RA/RJ	HLO8-53	121408	81.62	83.62	2.00	0.09	0.5	1.15	172	84	<0.5	<5	4.23	5	18	14	31	4.83	<1	0.28	<10	0.93	2731	<2	0.01	3	1856	81	2.46	<5	2	166	<5	<0.01	<10	<10	15	37	<10	348	2
8V3497RA/RJ	HLO8-53	121409	83.62	85.62	2.00	0.16	0.3	1.14	200	84	<0.5	<5	3.53	3	17	13	25	4.95	<1	0.28	<10	0.91	2493	<2	0.01	3	1669	18	2.03	<5	2	117	<5	<0.01	<10	<10	11	37	<10	55	2
8V3497RA/RJ	HLO8-53	121410	85.62	87.62	2.00	0.04	0.5	1.56	61	72	<0.5	<5	3.66	1	17	13	46	4.82	<1	0.23	<10	1.45	2969	<2	0.01	2	1661	95	1.03	<5	3	134	<5	<0.01	<10	<10	17	50	<10	177	2
8V3497RA/RJ	HLO8-53	121411	87.62	89.62	2.00	0.05	0.2	1.58	59	72	<0.5	<5	3.32	<1	19	8	36	5.17	<1	0.24	<10	1.29	2651	3	0.01	3	1832	22	1.27	<5	3	127	<5	<0.01	<10	<10	16	46	<10	92	2
8V3497RA/RJ	HLO8-53	121412	89.62	91.62	2.00	0.03	0.2	1.76	39	62	<0.5	<5	3.69	<1	20	7	50	4.83	<1	0.23	<10	1.55	2632	<2	0.02	2	1825	19	0.89	<5	3	139	<5	<0.01	<10	<10	15	47	<10	97	2
8V3497RA/RJ	HLO8-53	121413	91.62	93.13	1.51	0.07	0.4	1.01	133	76	<0.5	<5	4.60	3	16	13	28	5.02	<1	0.24	<10	0.98	2511	<2	0.01	2	1740	94	2.93	<5	2	204	<5	<0.01	<10	<10	12	30	<10	198	2
8V3497RA/RJ	HLO8-53	121414	93.13	94.66	1.53	0.05	0.5	1.00	151	93	<0.5	5	4.53	3	18	19	28	4.97	<1	0.26	<10	1.20	2878	<2	0.01	3	1689	56	2.45	<5	2	191	<5	<0.01	<10	<10	19	32	<10	161	2
8V3497RA/RJ	HLO8-53	121415	94.66	96.66	2.00	0.05	0.2	0.63	66	102	<0.5	<5	3.91	2	8	30	15	3.27	<1	0.26	<10	0.75	1877	2	0.01	1	882	114	1.48	<5	2	161	<5	<0.01	<10	<10	20	<10	186	3	
8V3497RA/RJ	HLO8-53	121416	96.66	98.66	2.00	0.02	<0.1	0.87	55	88	<0.5	<5	3.94	2	7	34	11	3.18	<1	0.23	<10	0.70																			

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																										
						Au g/t	Ag g/t	Al %	As ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm	
8V3497RA/RJ	HL08-53	121455	161.76	163.76	2.00	0.02	1.3	1.97	85	157	<0.5	<5	3.51	1	16	6	68	4.75	<1	0.28	<10	1.23	3537	<2	0.01	3	1504	23	0.65	<5	3	96	<5	0.02	<10	18	73	<10	104	2
8V3497RA/RJ	HL08-53	121456	163.76	165.74	1.98	0.04	0.9	1.93	155	111	<0.5	<5	2.58	2	18	4	42	5.01	<1	0.31	<10	1.11	3028	<2	0.01	3	1516	25	0.91	<5	3	72	<5	0.01	<10	16	66	<10	87	2
8V3497RA/RJ	HL08-53	121457	165.74	167.19	1.45	0.04	0.9	1.94	110	111	<0.5	<5	4.31	1	17	4	29	5.21	<1	0.30	<10	1.11	3181	<2	0.01	2	1462	18	1.18	<5	3	108	<5	0.04	<10	18	66	<10	69	2
8V3497RA/RJ	HL08-53	121458	167.19	168.56	1.37	0.02	0.8	2.12	102	106	<0.5	<5	4.18	1	18	4	26	5.75	<1	0.30	<10	1.24	3597	<2	0.01	3	1457	16	1.23	<5	3	158	<5	0.03	<10	20	68	<10	81	2
8V3497RA/RJ	HL08-53	121459	168.56	170.56	2.00	0.07	2.2	1.16	225	86	<0.5	<5	1.98	6	29	129	98	6.27	<1	0.25	<10	1.45	2654	<2	0.01	34	1748	176	2.09	<5	10	98	<5	<0.01	<10	20	121	<10	421	2
8V3497RA/RJ	HL08-53	121460	170.56	172.56	2.00	0.05	2.7	2.52	382	52	<0.5	<6	1.72	7	39	272	110	7.78	<1	0.13	<10	2.09	2538	<2	0.01	55	2221	137	2.92	<5	14	57	<5	0.02	<10	16	181	<10	159	3
8V3497RA/RJ	HL08-53	121461	172.56	174.56	2.00	0.05	1.8	2.56	237	101	<0.5	<5	1.29	4	39	238	117	7.51	<1	0.18	<10	2.08	2548	<2	0.01	46	2011	37	2.02	<5	14	40	<5	0.01	<10	13	184	<10	169	3
8V3497RA/RJ	HL08-53	121462	174.56	176.06	1.50	0.07	2.2	2.45	344	67	<0.5	<6	1.85	6	35	221	116	7.95	<1	0.18	<10	2.06	2342	<2	0.01	44	2068	24	3.01	<5	13	67	<5	0.01	<10	14	152	<10	110	3
8V3497RA/RJ	HL08-53	121463	176.06	177.58	1.52	0.04	1.5	2.65	219	92	<0.5	<5	1.61	3	44	256	118	6.85	<1	0.27	<10	1.99	2183	<2	0.01	45	2078	18	1.46	<5	14	46	<5	0.01	<10	10	173	<10	76	3
8V3497RA/RJ	HL08-53	121464	177.58	179.58	2.00	0.03	1.9	3.09	250	78	<0.5	<6	1.72	4	44	317	126	8.34	<1	0.16	<10	2.65	2284	<2	0.01	48	2255	16	2.41	<5	17	51	<5	0.02	<10	15	237	<10	112	3
8V3497RA/RJ	HL08-53	121465	179.59	181.27	1.68	0.03	2.2	3.04	454	83	<0.5	<5	4.03	8	37	312	109	8.00	<1	0.12	<10	2.76	2796	<2	0.01	40	2154	22	2.43	<5	19	96	<5	0.02	<10	16	213	<10	155	3
8V3497RA/RJ	HL08-53	121466	181.27	183.30	2.03	0.07	2.0	2.01	493	82	<0.5	<5	3.93	9	33	208	107	6.74	<1	0.19	<10	1.73	2400	<2	0.01	43	1914	17	3.60	<5	13	87	<5	0.03	<10	16	145	<10	120	3
8V3497RA/RJ	HL08-53	121467	183.30	185.30	2.00	0.01	1.6	2.15	134	52	<0.5	<5	8.21	2	28	264	86	5.03	<1	0.07	<10	2.21	2580	<2	0.01	35	1721	9	1.16	<5	15	393	<5	0.03	<10	12	196	<10	91	2
8V3497RA/RJ	HL08-53	121468	185.30	187.32	2.02	0.02	1.4	2.34	168	45	<0.5	<5	6.64	2	35	298	77	5.27	<1	0.06	<10	2.37	3126	<2	0.01	39	1794	14	0.87	<5	19	212	<5	0.06	<10	14	225	<10	76	2
8V3497RA/RJ	HL08-53	121469	187.32	189.32	2.00	0.01	2.2	2.81	165	48	<0.5	<5	8.91	2	39	330	114	6.46	<1	0.05	<10	2.94	3725	<2	0.01	46	2024	10	1.24	<5	29	275	<5	0.10	<10	18	256	<10	67	3
8V3497RA/RJ	HL08-53	121470	189.32	191.32	2.00	0.01	1.9	2.59	168	39	<0.5	<5	7.28	2	35	296	78	5.72	<1	0.04	<10	2.81	3828	<2	0.01	41	1817	9	1.20	<5	24	199	<5	0.08	<10	13	225	<10	69	3
8V3497RA/RJ	HL08-53	121471	191.32	193.32	2.00	0.02	1.9	2.51	215	44	<0.5	<5	7.21	4	36	286	97	5.90	<1	0.07	<10	2.63	2939	<2	0.01	42	1810	10	1.25	<5	22	218	<5	0.09	<10	14	212	<10	112	3
8V3497RA/RJ	HL08-53	121472	193.32	195.32	2.00	0.03	2.2	2.06	277	67	<0.5	<5	7.21	5	39	281	95	5.71	<1	0.12	<10	2.01	2745	<2	0.01	46	1976	12	1.84	<5	20	197	<5	0.10	<10	13	201	<10	77	3
8V3497RA/RJ	HL08-53	121473	195.32	197.32	2.00	0.02	1.8	2.28	189	49	<0.5	<5	6.46	3	34	295	103	5.52	<1	0.08	<10	2.34	2808	<2	0.01	41	1874	21	1.37	<5	19	148	<5	0.08	<10	11	219	<10	148	2
8V3497RA/RJ	HL08-53	121474	197.32	199.32	2.00	0.04	1.7	2.40	318	48	<0.5	<5	9.55	6	37	302	88	6.22	<1	0.08	<10	2.36	3714	<2	0.01	43	1910	43	1.78	<5	21	202	<5	0.07	<10	18	215	<10	130	3
8V3497RA/RJ	HL08-53	121475	Blank	Blank	<0.01	<0.1	0.99	5	242	10	<0.5	<5	0.77	<1	9	94	4	2.25	<1	0.41	<10	0.69	691	<2	0.06	7	813	2	0.03	<5	3	44	<5	0.13	<10	<10	<10	52	2	
8V3497RA/RJ	HL08-53	121476	199.32	201.32	2.00	0.01	1.3	2.28	147	57	<0.5	<5	10.16	2	37	293	84	5.38	<1	0.08	<10	2.16	3911	<2	0.01	42	1835	9	0.77	<5	22	252	<5	0.03	<10	17	208	<10	54	2
8V3497RA/RJ	HL08-53	121477	201.32	203.28	1.96	0.01	1.7	2.27	193	64	<0.5	<5	8.10	3	37	302	95	5.52	<1	0.08	<10	2.21	3691	<2	0.01	44	1891	13	0.98	<5	21	224	<5	0.06	<10	17	211	<10	79	2
8V3497RA/RJ	HL08-53	121478	203.28	204.26	0.98	0.06	2.6	1.31	301	74	<0.5	<5	12.53	5	27	149	65	5.21	<1	0.11	<10	1.18	4531	<2	0.01	34	1310	24	3.21	<5	11	216	<5	0.03	<10	20	100	<10	51	1
8V3497RA/RJ	HL08-53	121479	204.26	205.26	1.00	0.06	1.9	1.07	293	52	<0.5	<5	11.53	5	26	132	47	4.50	<1	0.16	<10	1.05	4094	<2	0.01	30	1371	21	3.51	<5	8	235	<5	0.04	<10	21	87	<10	58	1
8V3497RA/RJ	HL08-53	121480	205.26	206.44	1.18	0.11	6.3	1.86	601	57	<0.5	<7	7.03	11	35	177	89	9.01	<1	0.16	<10	1.99	6184	<2	0.01	42	1541	55	>5.00	8	9	164	<5	0.04	<10	42	115	<10	174	3
8V3497RA/RJ	HL08-53	121481	206.44	207.81	1.37	0.66	7.4	1.59	629	86	<0.5	<5	4.60	13	40	119	80	6.66	<1	0.24	<10	1.45	4861	<2	0.01	63	1890	216	>5.00	10	8	141	<5	0.01	<10	27	83	<11	623	2
8V3497RA/RJ	HL08-53	121482	207.81	209.16	1.35	0.28	6.5	1.49	913	102	<0.5	<6	6.68	17	36	122	55	7.09	<1	0.24	<10	1.42	5086	<2	0.01	50	2227	38	>5.00	16	8	196	<5	0.01	<10	29	83	<10	188	2
8V3497RA/RJ	HL08-53	121483	209.16	210.66	1.50	0.58	10.1	1.04	1018	57	<0.5	<9	6.21	19	35	83	52	10.74	<1	0.29	<10	0.78	3166	<2	0.01	46	2097	68	>5.00	28	6	170	<5	0.02	<10	28	50	<10	199	4
8V3497RA/RJ	HL08-53	121484	210.66	211.42	0.76	0.33	3.8	1.17	636	64	<0.5	<5	4.59	11	31	87	57	6.76	<1	0.23	<10	1.00	2151	<2	0.01	33	1647	22	>5.00	5	6	125	<5	0.						

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																										
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3497RA/RJ	HLO8-54	121526	9.40	10.45	1.05	<0.01	0.5	1.98	9	1291	<0.5	5	3.55	<1	20	51	38	5.92	<1	0.15	25	1.78	1204	<2	0.03	13	2963	13	0.29	<5	4	120	<5	0.01	<10	<10	78	<10	222	5
8V3497RA/RJ	HLO8-54	121527	10.45	12.45	2.00	0.04	0.7	2.09	83	115	<0.5	6	3.85	4	22	12	45	6.79	<1	0.20	<10	1.62	2935	<2	0.01	3	1739	280	2.00	<5	4	96	<5	0.01	<10	<10	89	<10	401	2
8V3497RA/RJ	HLO8-54	121528	12.45	13.70	1.25	0.07	2.1	1.89	120	136	<0.5	5	6.03	10	21	10	76	6.35	<1	0.14	<10	1.55	3551	<2	0.01	2	1623	1035	2.35	<5	4	147	<5	0.01	<10	18	97	17	1065	2
8V3497RA/RJ	HLO8-54	121529	13.70	15.63	1.93	0.05	1.9	1.86	66	97	<0.5	5	4.79	17	21	7	108	6.29	<1	0.18	<10	1.46	3237	6	0.01	2	1702	1215	2.05	<5	4	160	<5	0.01	<10	20	73	30	1903	2
8V3497RA/RJ	HLO8-54	121530	15.63	16.66	1.03	0.02	0.9	2.15	22	111	<0.5	<5	3.58	<1	22	5	92	6.88	<1	0.18	<10	1.52	2368	19	0.02	2	1837	39	0.62	<5	7	119	<5	0.02	<10	13	100	<10	145	3
8V3497RA/RJ	HLO8-54	121531	19.80	20.88	1.08	0.02	0.3	2.31	40	82	<0.5	<5	3.36	1	24	6	38	6.67	<1	0.18	<10	1.87	2839	<2	0.01	2	1843	80	1.17	<5	5	155	<5	0.07	<10	18	97	<10	161	3
8V3497RA/RJ	HLO8-54	121532	20.88	22.00	1.12	0.15	1.5	1.61	337	88	<0.5	7	7.63	22	19	15	23	7.47	<1	0.17	<10	1.27	4468	2	0.01	2	1418	492	4.86	<5	3	188	<5	0.01	<10	29	63	33	2030	3
8V3497RA/RJ	HLO8-54	121533	22.00	23.00	1.00	0.22	7.8	1.07	383	63	<0.5	9	7.04	198	18	21	343	8.37	<1	0.12	<10	0.84	3622	<2	0.01	2	1068	4884	>5.00	<5	2	145	<5	0.01	<10	23	53	369	19700	3
8V3497RA/RJ	HLO8-54	121534	23.00	24.00	1.00	0.23	4.0	1.07	402	83	<0.5	7	5.30	109	20	22	107	7.91	<1	0.10	<10	0.88	3209	<2	0.01	3	1003	1587	>5.00	<5	2	102	<5	0.01	<10	22	66	201	11300	3
8V3498RA/RJ	HLO8-54	121535	24.00	25.00	1.00	0.18	7.1	0.75	572	46	<0.5	9	5.58	138	14	43	374	6.75	<1	0.12	<10	0.53	3195	2	0.01	3	771	2631	>5.00	<5	2	166	<5	0.01	<10	25	34	254	15300	2
8V3498RA/RJ	HLO8-54	121536	25.00	26.00	1.00	0.30	3.9	0.85	263	91	<0.5	7	7.07	44	9	38	52	4.33	<1	0.17	<10	0.54	3399	4	0.01	2	901	3517	4.01	<5	2	145	<5	0.01	<10	16	33	68	4214	1
8V3498RA/RJ	HLO8-54	121537	26.00	26.98	0.98	0.36	1.3	1.04	163	117	<0.5	<5	5.29	5	10	29	27	3.28	<1	0.24	<10	0.59	3227	3	0.01	2	961	376	1.96	<5	2	110	<5	0.01	<10	17	35	<10	231	1
8V3498RA/RJ	HLO8-54	121538	26.98	29.07	2.09	0.08	1.0	1.47	146	107	<0.5	<5	2.95	9	14	16	40	4.09	<1	0.30	<10	0.92	2962	9	0.01	2	1205	146	2.00	<5	2	65	<5	0.04	<10	16	46	12	710	1
8V3498RA/RJ	HLO8-54	121539	29.07	30.00	0.93	0.32	11.2	1.16	407	41	<0.5	10	3.97	241	16	43	498	8.14	1	0.12	<10	0.83	3286	23	0.01	2	685	4843	>5.00	<5	2	88	<5	0.02	<10	26	47	458	26100	3
8V3498RA/RJ	HLO8-54	121540	30.00	31.00	1.00	0.18	1.7	1.28	259	51	<0.5	5	4.79	26	12	26	43	5.10	<1	0.10	<10	1.00	3543	33	0.01	1	834	399	3.79	<5	2	100	<5	0.04	<10	19	49	39	2491	1
8V3498RA/RJ	HLO8-54	121541	31.00	32.00	1.00	0.14	3.8	1.43	214	57	<0.5	7	6.33	77	14	23	142	5.60	<1	0.11	<10	1.10	3940	2	0.01	2	847	1229	4.33	<5	3	114	<5	0.02	<10	21	56	134	8055	1
8V3498RA/RJ	HLO8-54	121542	32.00	32.80	0.80	0.07	0.7	1.04	121	112	<0.5	<5	5.04	4	7	19	16	2.71	<1	0.27	<10	0.56	2821	<2	0.01	1	1110	71	1.19	<5	2	110	<5	<0.01	<10	14	21	<10	231	1
8V3498RA/RJ	HLO8-54	121543	32.80	34.67	1.87	0.06	1.6	1.13	133	89	<0.5	5	6.93	5	8	32	25	3.14	<1	0.17	<10	0.82	4026	2	0.01	1	874	272	1.57	<5	3	122	<5	0.01	<10	16	36	<10	375	2
8V3498RA/RJ	HLO8-54	121544	34.67	36.13	1.46	0.11	12.3	3.01	157	43	<0.5	<5	6.41	13	32	205	301	6.85	<1	0.15	<10	3.08	7567	<2	0.01	31	1677	2619	3.40	<5	15	132	<5	0.08	<10	42	145	44	2715	1
8V3498RA/RJ	HLO8-54	121545	36.13	38.00	1.87	0.03	3.1	2.34	85	54	<0.5	<5	7.80	3	29	195	195	5.04	<1	0.12	<10	2.12	6837	<2	0.01	32	1374	386	1.37	<5	13	132	<5	0.05	<10	35	109	10	416	1
8V3498RA/RJ	HLO8-54	121546	38.00	39.20	1.20	0.02	1.5	2.18	49	44	<0.5	<5	7.36	2	33	214	34	3.82	<1	0.12	<10	1.81	6495	<2	0.01	37	1621	226	0.54	<5	14	186	<5	0.07	<10	34	113	17	484	3
8V3498RA/RJ	HLO8-54	121547	39.20	41.00	1.80	0.03	1.8	2.47	48	41	<0.5	<5	8.62	1	34	252	91	4.93	<1	0.07	<10	2.41	7040	<2	0.01	39	1809	149	1.06	<5	14	229	<5	0.09	<10	33	172	<10	221	3
8V3498RA/RJ	HLO8-54	121548	41.00	43.00	2.00	0.02	1.5	2.44	48	36	<0.5	<5	9.62	2	33	249	41	4.85	<1	0.10	<10	2.30	6596	<2	0.01	37	1577	160	0.67	<5	19	160	<5	0.07	<10	30	172	<10	281	1
8V3498RA/RJ	HLO8-54	121549	43.00	45.00	2.00	0.02	2.6	2.57	47	40	<0.5	<5	7.77	3	37	281	120	4.69	<1	0.07	<10	2.60	7570	<2	0.01	42	1888	463	0.73	<5	18	162	<5	0.10	<10	35	178	12	624	2
8V3498RA/RJ	HLO8-54	121550	Blank	Blank	<0.01	<0.1	1.09	<5	257	<0.5	<5	1.00	<1	10	96	2	2.21	<1	0.49	<10	0.74	992	<2	0.08	7	903	13	0.02	<5	3	55	<5	0.15	<10	<10	48	<10	74	2	
8V3498RA/RJ	HLO8-54	121551	45.00	47.00	2.00	0.02	2.4	2.33	53	53	<0.5	<5	9.48	2	34	308	191	5.17	<1	0.06	<10	2.34	6130	<2	0.01	39	1893	170	1.17	<5	24	166	<5	0.08	<10	25	216	<10	257	2
8V3498RA/RJ	HLO8-54	121552	47.00	49.00	2.00	0.05	1.8	2.21	66	48	<0.5	<5	8.48	2	35	252	110	4.85	<1	0.05	<10	2.34	5367	<2	0.01	40	1785	65	1.43	<5	13	214	<5	0.08	<10	22	156	<10	140	3
8V3498RA/RJ	HLO8-54	121553	49.00	50.22	1.22	0.02	1.3	1.51	49	44	<0.5	<5	7.62	1	34	228	142	3.37	<1	0.05	<10	1.60	3884	<2	0.01	33	1825	31	1.13	<5	10	184	<5	0.11	<10	14	125	<10	70	4
8V3498RA/RJ	HLO8-54	121554	50.22	51.45	1.23	0.02	1.3	1.92	70	48	<0.5	<5	7.90	1	40	244	71	4.41	<1	0.04	<10	1.95	4856	<2	0.01	43	1863	67	1.43	<5	13	189	<5	0.10	<10	20	152	<10	99	4
8V3498RA/RJ	HLO8-54	121555	51.45	53.43	1.98	0.19	2.2	1.80	1103	35	<0.5	<5	8.66	33	27	163	168	3.92	<1	0.06	<10	1.49	4944	<2	0.01	28	1324	446	1.08	<5	10	215	<5	0.07	<10	21	107	14	871	3
8V3498RA/RJ	HLO8-54	121556	53.43	55.39	1.96	0.01	1.3	1.87	72	134	<0.5	<5	8.50	2	30	179	18	4.02	<1	0.12	<10	1.39	6550	<2	0.01	32	1546	93	0.31	<5	12	183	<5	0.05	<10	29	109	<10	148	2
8V3498RA/RJ	HLO8-54	121557	55.39	57.40	2.01	0.02	4.8	2.72	112	54	<0.5	5	9.72	12	33	247	150	5.73	<1	0.11	<10	2.31	8090	<2	0.01	40	1770	1188	1.17	<5	19	169	<5	0.06	<10	43	176	28	1590	2
8V3498RA/RJ	HLO8-54	121558	57.40	59.40	2.00	0.16	4.1	2.42	1942	40	<0.5	6	9.36	63	28	250	161	5.44	<1	0.07	<10	2.11	7053	<2	0.01	34	1561	1130	1.50	<5	21	146	<5	0.04	<10	35	181	29	1783	1
8V3498RA/RJ	HLO8-54	121559	59.40	61.50	2.10	0.35	5.7	3.14	6306	37	<0.5	8	8.35	189	27	246	204	6.42	<1	0.08	<10	2.88	8437																	

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn: 2500-5000										5000-10000				>10000													
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3498RA/RJ	HL08-54	121598	127.00	128.50	1.50	0.07	0.9	2.79	66	111	<0.5	7	8.68	1	32	260	130	5.63	1	0.13	<10	3.28	2174	<2	0.01	39	1809	15	0.69	<5	21	208	<5	<0.01	<10	12	183	<10	71	2
8V3498RA/RJ	HL08-54	121599	128.50	130.50	2.00	0.02	1.5	2.20	90	73	<0.5	7	9.08	2	36	253	108	5.35	1	0.14	<10	2.65	2357	<2	0.01	42	1795	12	0.62	<5	24	250	<5	<0.01	<10	13	182	<10	77	2
8V3498RA/RJ	HL08-54	121600	Blank	Blank	<0.01	<0.1	1.16		<5	258	<0.5	<5	1.09	<1	10	113	3	2.35	1	0.52	<10	0.82	721	<2	0.07	8	844	5	0.03	<5	4	60	<5	0.14	<10	<10	52	<10	55	2
8V3498RA/RJ	HL08-54	121601	130.50	132.50	2.00	0.02	1.4	2.23	109	54	<0.5	<5	9.60	2	33	277	86	5.07	1	0.10	<10	2.09	2761	<2	0.01	37	1774	15	0.92	<5	22	215	<5	0.06	<10	12	213	<10	114	3
8V3498RA/RJ	HL08-54	121602	132.50	134.50	2.00	0.01	1.7	1.80	77	66	<0.5	<5	11.13	2	35	287	89	4.23	1	0.10	<10	1.85	2641	<2	0.01	38	1780	15	1.13	<5	23	180	<5	0.12	<10	<10	210	<10	74	3
8V3498RA/RJ	HL08-54	121603	134.50	136.11	1.61	0.01	1.6	1.82	75	75	<0.5	<5	6.06	1	33	231	93	4.32	1	0.13	<10	1.95	1579	<2	0.01	33	1790	13	0.94	<5	10	104	<5	0.13	<10	<10	157	<10	57	4
8V3498RA/RJ	HL08-54	121604	136.11	137.28	1.17	0.01	2.0	1.12	71	62	<0.5	<5	8.59	2	35	280	99	5.10	1	0.10	<10	2.01	2319	<2	0.01	39	1861	10	1.02	<5	19	153	<5	0.13	<10	<10	207	<10	72	4
8V3498RA/RJ	HL08-54	121605	137.28	138.46	1.18	0.02	3.0	1.83	87	64	<0.5	<5	9.51	2	38	311	147	4.74	1	0.10	<10	1.67	2805	<2	0.01	41	1988	12	1.36	<5	27	168	<5	0.12	<10	<10	236	<10	58	4
8V3498RA/RJ	HL08-54	121606	138.46	139.60	1.14	0.03	0.6	1.59	44	92	<0.5	>	>15.00	1	19	179	47	3.60	<1	0.09	<10	1.33	3766	<2	0.01	26	1102	14	0.45	<5	16	288	<5	0.01	<10	<10	187	<10	42	1
8V3498RA/RJ	HL08-54	121607	139.60	140.85	1.25	0.03	1.4	2.12	91	64	<0.5	5	12.59	2	36	240	115	5.19	1	0.12	<10	1.87	2339	<2	0.01	38	1587	11	1.31	<5	21	242	<5	0.05	<10	13	176	<10	46	4
HL08-55 - Zone: Big K, Pad 36: 434759E,6224083N, Elev:1080m, Az: 021, Dip: -60, EOH:477.74m																																								
8V3633RA/RJ	HL08-55	122626	1.58	3.46	1.88	0.01	0.3	1.85	20	78	<0.5	<5	4.05	1	16	16	40	4.11	<1	0.36	10	1.12	1678	<2	0.01	2	1410	50	0.68	10	2	119	<5	0.11	<10	<10	45	<10	115	3
8V3633RA/RJ	HL08-55	122627	3.46	5.12	1.66	0.01	0.1	1.96	15	73	<0.5	<5	3.51	<1	17	15	33	4.38	<1	0.24	<10	1.15	1648	<2	0.02	2	1420	23	0.19	10	4	132	<5	0.12	<10	<10	58	<10	70	3
8V3497RA/RJ	HL08-55	130199	5.12	7.06	1.94	0.01	<0.1	2.08	12	72	<0.5	<5	4.36	<1	19	6	35	5.11	<1	0.15	<10	1.52	2084	<2	0.01	3	1786	14	0.12	<5	3	124	<5	0.04	<10	13	62	<10	95	2
8V3497RA/RJ	HL08-55	130200	Blank	Blank	0.01	<0.1	0.84		8	245	<0.5	<5	0.54	<1	8	78	4	2.19	<1	0.31	<10	0.65	585	<2	0.04	6	817	4	0.05	<5	2	31	<5	0.11	<10	<10	39	<10	55	1
8V3497RA/RJ	HL08-55	130201	7.06	8.59	1.53	0.01	<0.1	2.03	10	71	<0.5	<5	2.94	<1	19	5	16	5.23	<1	0.14	<10	1.49	2070	<2	0.01	3	1767	18	0.08	<5	2	95	<5	0.04	<10	13	57	<10	109	2
8V3497RA/RJ	HL08-55	130202	8.59	10.09	1.50	0.01	<0.1	1.88	8	79	<0.5	<5	2.42	<1	18	8	25	5.01	<1	0.15	10	1.32	2008	<2	0.01	3	1688	24	0.08	<5	3	82	<5	0.05	<10	12	53	<10	125	2
8V3633RA/RJ	HL08-55	122628	10.09	11.29	1.20	0.04	0.2	2.17	22	74	<0.5	<5	3.47	<1	18	10	44	4.59	<1	0.29	<10	1.36	1672	<2	0.02	2	1400	40	0.24	10	3	100	<5	0.10	<10	<10	59	<10	87	2
8V3633RA/RJ	HL08-55	122629	11.29	12.11	0.82	0.04	0.3	2.08	44	76	<0.5	<5	3.54	1	19	9	32	4.85	<1	0.26	10	1.31	1750	<2	0.02	2	1470	45	0.44	10	3	103	<5	0.09	<10	<10	61	<10	92	2
8V3633RA/RJ	HL08-55	122630	12.11	13.21	1.10	0.01	0.2	2.07	33	54	<0.5	<5	5.36	<1	17	11	37	4.64	<1	0.26	<10	1.37	1874	<2	0.02	2	1401	27	0.31	9	3	124	<5	0.08	<10	<10	60	<10	93	2
8V3633RA/RJ	HL08-55	122631	13.21	14.33	1.12	0.02	0.2	2.18	22	55	<0.5	<5	4.58	<1	18	19	49	4.66	<1	0.23	<10	1.50	2064	<2	0.02	2	1479	35	0.21	10	4	155	<5	0.10	<10	<10	72	<10	100	2
8V3633RA/RJ	HL08-55	122632	14.33	15.15	0.82	0.01	0.3	2.16	15	68	<0.5	<5	3.63	<1	19	8	58	5.09	<1	0.25	<10	1.42	1957	<2	0.02	2	1579	37	0.48	10	3	136	<5	0.10	<10	<10	69	<10	102	3
8V3497RA/RJ	HL08-55	130203	15.15	16.67	1.52	0.08	0.2	2.03	36	83	<0.5	<5	2.38	<1	20	13	40	5.60	<1	0.15	<10	1.48	2167	<2	0.01	3	1635	29	0.42	5	2	87	<5	0.03	<10	13	56	<10	106	2
8V3497RA/RJ	HL08-55	130204	16.67	18.04	1.37	0.04	0.2	2.32	24	61	<0.5	<5	3.36	<1	22	9	46	5.83	<1	0.16	10	1.81	2884	<2	<0.01	4	1773	48	0.39	<5	2	101	<5	0.03	<10	17	53	<10	137	2
8V3633RA/RJ	HL08-55	122633	18.04	19.21	1.17	0.02	0.4	2.30	44	93	<0.5	<5	4.32	<1	19	15	7	4.57	<1	0.34	<10	1.66	2647	<2	0.01	2	1545	50	0.44	11	3	108	<5	0.12	<10	<10	57	<10	84	2
8V3633RA/RJ	HL08-55	122634	19.21	20.65	1.44	0.02	0.6	2.47	106	127	<0.5	<5	4.56	2	18	16	9	5.09	<1	0.35	11	1.69	2680	<2	0.01	2	1596	87	0.58	11	3	122	<5	0.10	<10	<10	57	<10	90	2
8V3633RA/RJ	HL08-55	122635	20.65	22.35	1.70	0.04	0.6	2.11	63	97	<0.5	<5	4.14	1	18	15	25	4.29	<1	0.36	<10	1.30	2414	<2	0.01	2	1450	67	0.58	11	3	117	<5	0.11	<10	<10	51	<10	92	2
8V3633RA/RJ	HL08-55	122636	22.35	23.88	1.53	0.01	0.4	2.45	41	111	<0.5	<5	4.68	<1	21	11	46	5.21	<1	0.28	<10	1.65	2428	<2	0.02	2	1658	44	0.43	13	5	117	<5	0.15	<10	<10	88	<10	95	3
8V3633RA/RJ	HL08-55	122637	23.88	25.00	1.12	0.01	0.5	2.46	57	68	<0.5	<5	4.12	1	22	10	41	5.57	<1	0.23	<10	1.66	2098	<2	0.02	2	1749	41	0.55	13	4	102	<5	0.14	<10	<10	86	<10	96	3
8V3633RA/RJ	HL08-55	122638	25.00	26.00	1.00	0.01	0.6	2.37	51	101	<0.5	<5	3.40	<1	22	16	48	5.32	<1	0.33	10	1.52	2130	<2	0.02	2	1758	32	0.41	13	4	83	<5	0.15	<10	<10	72	<10	85	3
8V3633RA/RJ	HL08-55	122639	26.00	27.06	1.06	0.02	0.6	2.25	107	101	<0.5	<5	4.15	2	21	12	53	5.16	<1	0.28	10	1.57	2294	<2	0.02	2	1724	40	0.79	12	4	103	<5	0.1						

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																												
					1.0-3.0	3.0-5.0	>5.0	5-10	10-50	50-100	>100	2500-5000	5000-10000	>10000	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Zr															
8V3498RA/RJ	HL08-55	130246	86.60	88.10	1.50	0.02	0.3	2.11	37	71	<0.5	<5	3.26	1	21	8	28	4.82	<1	0.26	<10	1.36	2552	<2	0.02	3	1593	10	0.88	<5	5	146	<5	0.18	<10	15	62	<10	79	5	
8V3498RA/RJ	HL08-55	130247	88.10	89.60	1.50	0.01	0.2	2.22	<5	75	<0.5	<5	2.98	<1	22	9	37	4.62	<1	0.21	<10	1.46	2151	<2	0.03	3	1678	7	0.32	<5	5	163	<5	0.19	<10	10	74	<10	82	6	
8V3498RA/RJ	HL08-55	130248	89.60	91.10	1.50	0.01	0.3	2.34	<5	59	<0.5	<5	2.85	<1	23	8	63	4.99	<1	0.21	<10	1.60	2334	<2	0.03	3	1762	5	0.26	<5	5	152	<5	0.16	<10	11	81	<10	93	5	
8V3498RA/RJ	HL08-55	130249	91.10	92.57	1.47	0.01	0.3	2.39	5	69	<0.5	<5	3.45	<1	23	4	35	4.93	<1	0.27	<10	1.71	2648	<2	0.01	3	1684	24	0.44	<5	5	130	<5	0.18	<10	14	62	<10	106	4	
8V3498RA/RJ	HL08-55	130250	Blank	Blank			<0.01	<0.1	1.00	<5	263	<0.5	<5	0.54	<1	9	65	1	2.09	<1	0.51	<10	0.63	619	<2	0.06	5	811	3	0.01	<5	3	48	<5	0.16	<10	<10	42	<10	51	2
8V3498RA/RJ	HL08-55	130251	92.57	94.10	1.53	0.01	0.4	2.44	31	109	<0.5	<5	3.98	1	26	5	51	5.40	<1	0.31	<11	1.80	2903	<2	0.02	3	1830	16	0.73	<5	5	119	<5	0.21	<10	14	75	<10	141	4	
8V3498RA/RJ	HL08-55	130252	94.10	95.60	1.50	0.01	0.3	2.32	34	92	<0.5	<5	3.30	<1	23	8	33	5.19	<1	0.29	<10	1.58	2461	<2	0.02	3	1652	8	0.61	<5	5	114	<5	0.17	<10	12	74	<10	93	3	
8V3498RA/RJ	HL08-55	130253	95.60	97.10	1.50	<0.01	0.2	2.11	19	70	<0.5	<5	5.21	<1	17	5	27	4.56	<1	0.29	<10	1.41	2232	<2	0.01	3	1631	9	0.38	<5	4	147	<5	0.06	<10	13	61	<10	91	2	
8V3498RA/RJ	HL08-55	130254	97.10	98.60	1.50	0.01	0.3	2.36	25	72	<0.5	<5	3.53	<1	23	5	44	5.41	<1	0.22	<10	1.72	2328	<2	0.02	3	1639	12	0.46	<5	4	96	<5	0.13	<10	12	70	<10	110	3	
8V3498RA/RJ	HL08-55	130255	98.60	100.10	1.50	0.01	0.4	2.39	12	81	<0.5	<5	3.63	<1	24	5	57	5.22	<1	0.31	<10	1.72	2462	<2	0.01	4	1737	26	0.55	<5	5	120	<5	0.15	<10	13	73	<10	124	3	
8V3498RA/RJ	HL08-55	130256	100.10	101.60	1.50	0.01	<0.1	2.65	<5	76	<0.5	<5	3.42	<1	25	7	47	5.60	<1	0.28	<10	1.76	2252	<2	0.02	4	1780	7	0.25	<5	6	136	<5	0.16	<10	14	87	<10	103	4	
8V3498RA/RJ	HL08-55	130257	101.60	103.10	1.50	0.01	<0.1	2.54	<5	71	<0.5	<5	3.63	<1	25	4	40	5.49	<1	0.26	<10	1.77	2315	<2	0.02	4	1779	13	0.32	<5	5	143	<5	0.15	<10	13	79	<10	111	4	
8V3498RA/RJ	HL08-55	130258	103.10	104.60	1.50	0.01	<0.1	2.34	<5	62	<0.5	<5	3.54	<1	23	5	44	4.99	<1	0.21	<10	1.76	2150	<2	0.02	3	1756	13	0.31	<5	5	127	<5	0.16	<10	12	81	<10	108	4	
8V3498RA/RJ	HL08-55	130259	104.60	106.10	1.50	<0.01	<0.1	2.59	<5	56	<0.5	<5	3.50	<1	25	4	40	5.87	<1	0.18	<10	1.89	2165	<2	0.02	4	1744	3	0.22	<5	7	113	<5	0.20	<10	13	99	<10	95	4	
8V3498RA/RJ	HL08-55	130260	106.10	107.60	1.50	0.01	<0.1	2.36	16	76	<0.5	<5	4.66	<1	22	5	38	5.05	<1	0.28	<10	1.60	2566	<2	0.01	3	1582	13	0.52	<5	5	142	<5	0.18	<10	15	73	<10	85	4	
8V3498RA/RJ	HL08-55	130261	107.60	109.10	1.50	0.01	0.2	2.46	24	71	<0.5	<5	3.71	<1	24	4	40	5.47	<1	0.29	<10	1.69	2648	<2	0.02	4	1665	14	0.54	<5	5	104	<5	0.18	<10	11	81	<10	97	3	
8V3498RA/RJ	HL08-55	130262	109.10	110.60	1.50	0.03	0.2	2.34	64	82	<0.5	<5	4.10	1	22	5	33	5.27	<1	0.30	<10	1.59	2906	<2	0.01	3	1688	14	0.70	<5	5	110	<5	0.18	<10	15	77	<10	79	3	
8V3498RA/RJ	HL08-55	130263	110.60	112.31	1.71	0.02	0.2	2.38	47	85	<0.5	<5	4.24	1	23	4	49	5.55	<1	0.31	<10	1.56	2795	<2	0.01	3	1708	14	0.90	<5	5	130	<5	0.18	<10	15	79	<10	99	3	
8V3498RA/RJ	HL08-55	130264	112.31	113.80	1.49	0.02	<0.1	2.34	40	75	<0.5	<5	4.22	1	21	6	34	5.20	<1	0.30	<10	1.55	2216	<2	0.02	3	1696	10	0.54	<5	5	116	<5	0.15	<10	14	72	<10	82	3	
8V3498RA/RJ	HL08-55	130265	113.80	115.30	1.50	0.01	<0.1	2.34	20	75	<0.5	<5	6.16	<1	19	4	44	5.00	<1	0.34	12	1.50	2462	<2	0.02	3	1615	<2	0.40	<5	5	137	<5	0.08	<10	14	66	<10	71	2	
8V3498RA/RJ	HL08-55	130266	115.30	116.53	1.23	0.06	0.2	1.69	166	85	<0.5	<5	5.79	4	16	9	21	4.02	<1	0.37	<10	1.03	2418	<2	0.01	2	1520	18	1.37	<5	4	139	<5	0.09	<10	<10	46	<10	46	2	
8V3498RA/RJ	HL08-55	130267	116.53	118.18	1.65	0.02	<0.1	2.26	81	94	<0.5	<5	5.72	2	20	6	23	4.98	<1	0.44	11	1.37	2615	<2	0.02	3	1785	31	0.84	<5	4	134	<5	0.13	<10	14	58	<10	70	3	
8V3498RA/RJ	HL08-55	130268	118.18	119.82	1.64	0.01	<0.1	2.32	47	86	<0.5	<5	4.50	1	21	7	34	5.43	<1	0.36	<10	1.53	2468	<2	0.02	3	1761	31	1.06	<5	4	122	<5	0.07	<10	10	68	<10	98	3	
8V3498RA/RJ	HL08-55	130269	119.82	120.92	1.10	0.06	0.4	1.86	111	76	<0.5	5	7.81	3	18	6	38	4.75	<1	0.31	<10	1.33	3061	<2	0.01	3	1585	77	1.46	<5	5	204	<5	0.01	<10	17	58	<10	201	2	
8V3498RA/RJ	HL08-55	130270	120.92	122.26	1.34	0.02	<0.1	2.38	18	75	<0.5	<5	5.78	<1	26	6	34	5.15	<1	0.32	<10	1.56	2483	12	0.02	4	1765	5	0.49	<5	5	134	<5	0.09	<10	14	78	<10	90	3	
8V3498RA/RJ	HL08-55	130271	122.26	123.79	1.53	<0.01	<0.1	2.02	6	80	<0.5	<5	4.23	<1	17	7	29	4.34	<1	0.31	11	1.25	2191	<2	0.02	2	1647	<2	0.22	<5	4	134	<5	0.11	<10	<10	61	<10	69	3	
8V3498RA/RJ	HL08-55	130272	123.79	125.39	1.60	0.01	<0.1	1.98	12	90	<0.5	<5	5.19	<1	17	5	26	4.59	<1	0.27	11	1.21	2014	<2	0.03	2	1519	<2	0.38	<5	4	161	<5	0.04	<10	<10	60	<10	69	2	
8V3498RA/RJ	HL08-55	130273	125.39	127.00	1.61	0.01	<0.1	2.28	39	91	<0.5	<5	4.81	<1	21	5	42	5.02	<1	0.34	10	1.51	2359	<2	0.02	2	1723	13	0.50	<5	4	138	<5	0.01	<10	<10	66	<10	97	2	
8V3498RA/RJ	HL08-55	130274	127.00	128.50	1.50	0.05	1.0	1.95	84	91	<0.5	<5	4.29	3	19	5	45	5.18	<1	0.33	<10	1.21	2806	<2	0.01	3	1613	222	1.53	<5	3	108	<5	0.01	<10	16	58	<10	357	2	
8V3498RA/RJ	HL08-55	130275	Std	PM197			0.50	<0.1	1.09	6838	25	<0.5	16	6.33	166	185	15	71	3.88	<1	0.06	13	0.25	826	15	0.09	33	1400	9	1.39	<5	2	97	<5	0.07	<10	<10	44	<10	91	12
8V3498RA/RJ	HL08-55	130276	128.50	130.00	1.50	0.06	0.8	0.98	148	254																															

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3551RA/RJ	HL08-55	130318	188.20	189.70	1.50	0.05	1.6	2.23	380	147	<0.5	6	7.11	9	24	37	75	5.62	<1	0.25	<1.0	2.02	2476	<2	0.02	12	1880	9	2.10	<5	6	261	<5	<0.01	<10	18	77	<10	80	2
8V3551RA/RJ	HL08-55	130319	189.70	191.16	1.46	0.03	1.4	2.57	160	166	<0.5	5	5.03	3	25	40	78	5.38	<1	0.28	<1.0	2.22	1973	<2	0.02	11	2050	7	1.55	<5	6	210	<5	<0.01	<10	16	81	<10	93	2
8V3551RA/RJ	HL08-55	130320	191.16	192.70	1.54	0.04	1.6	2.81	559	140	<0.5	5	4.28	13	25	35	91	5.57	<1	0.23	<1.0	2.41	2085	<2	0.02	12	1923	6	0.97	<5	6	180	<5	<0.01	<10	15	82	<10	120	2
8V3551RA/RJ	HL08-55	130321	192.70	194.21	1.51	0.06	1.9	2.01	387	155	<0.5	5	4.31	9	26	38	87	5.55	<1	0.29	<1.0	1.55	1691	<2	0.02	13	1876	14	2.92	<5	5	146	<5	<0.01	<10	14	58	<10	96	2
8V3551RA/RJ	HL08-55	130322	194.21	195.70	1.49	0.03	1.4	2.35	341	130	<0.5	5	4.62	8	25	30	92	5.41	<1	0.25	<1.0	1.92	1771	<2	0.01	12	1844	9	1.83	<5	5	178	<5	<0.01	<10	15	68	<10	95	2
8V3551RA/RJ	HL08-55	130323	195.70	197.20	1.50	0.02	1.3	2.87	214	177	<0.5	7	10.07	5	26	38	93	5.60	<1	0.42	<1.0	2.10	2887	<2	0.01	12	1969	7	1.58	<5	7	364	<5	<0.01	<10	20	80	<10	82	2
8V3551RA/RJ	HL08-55	130324	197.20	198.73	1.53	0.03	1.3	2.56	253	139	<0.5	6	6.40	6	25	28	90	5.75	<1	0.30	<1.0	2.04	2077	<2	0.01	12	1954	8	2.09	<5	6	245	<5	<0.01	<10	18	71	<10	96	2
8V3551RA/RJ	HL08-55	130325	Std	PM922		6.86	3.0	1.63	786	163	<0.5	189	9.17	19	53	78	506	6.29	13	0.21	13	38	996	151	0.04	80	1056	93	2.47	<5	4	128	<5	0.15	<10	<10	45	55	101	19
8V3551RA/RJ	HL08-55	130326	198.73	200.10	1.37	0.04	1.4	2.23	295	139	<0.5	7	4.99	7	26	28	96	5.91	<1	0.30	<1.0	1.78	1732	<2	0.01	12	2018	11	3.09	<5	5	203	<5	<0.01	<10	17	62	<10	105	3
8V3551RA/RJ	HL08-55	130327	200.10	201.58	1.48	0.04	1.5	1.99	191	109	<0.5	5	6.29	4	20	27	90	4.52	<1	0.25	<1.0	1.63	2061	<2	0.01	10	1595	7	1.82	<5	5	237	<5	<0.01	<10	11	57	<10	54	2
8V3551RA/RJ	HL08-55	130328	201.58	203.16	1.58	0.02	1.3	2.34	214	128	<0.5	5	5.79	5	24	31	88	5.28	<1	0.30	<1.0	1.96	2044	<2	0.01	11	1801	8	1.83	<5	6	234	<5	<0.01	<10	17	68	<10	73	2
8V3551RA/RJ	HL08-55	130329	203.16	204.66	1.50	0.04	1.5	2.10	272	120	<0.5	5	6.70	6	22	26	78	4.99	<1	0.24	<1.0	1.81	2534	<2	0.01	11	1750	10	1.75	<5	6	276	<5	<0.01	<10	19	62	<10	68	2
8V3551RA/RJ	HL08-55	130330	204.66	206.12	1.46	0.08	2.2	1.86	581	153	<0.5	5	6.39	13	24	24	81	5.34	<1	0.29	<1.0	1.48	2499	<2	0.01	11	1825	15	3.15	<5	6	234	<5	<0.01	<10	19	53	<10	60	2
8V3551RA/RJ	HL08-55	130331	206.12	207.60	1.48	0.03	1.4	2.24	196	109	<0.5	5	6.22	4	20	23	84	4.96	<1	0.25	<1.0	1.80	2093	<2	0.01	10	1669	7	1.71	<5	5	228	<5	0.01	<10	17	57	<10	65	2
8V3551RA/RJ	HL08-55	130332	207.60	209.10	1.50	0.02	1.5	2.24	224	122	<0.5	5	6.42	5	24	40	91	4.96	<1	0.26	<1.0	1.85	2092	<2	0.01	13	1808	7	1.86	<5	6	252	<5	0.01	<10	16	67	<10	78	2
8V3551RA/RJ	HL08-55	130333	209.10	210.60	1.50	0.07	1.8	2.04	438	170	<0.5	7	6.00	10	30	37	82	6.64	<1	0.39	<1.0	1.55	1958	3	0.01	14	2164	16	4.66	<5	6	210	<5	0.01	<10	13	61	<10	108	3
8V3551RA/RJ	HL08-55	130334	210.60	212.10	1.50	0.04	1.6	1.97	479	130	<0.5	5	6.02	11	25	26	83	5.98	<1	0.28	<1.0	1.64	1930	<2	0.01	12	1772	14	3.96	<5	5	258	<5	0.01	<10	18	55	<10	77	3
8V3551RA/RJ	HL08-55	130335	212.10	213.57	1.47	0.02	1.1	2.77	270	117	<0.5	5	6.01	6	23	31	84	5.43	<1	0.26	<1.0	2.29	2200	<2	0.01	11	1805	6	1.35	<5	6	264	<5	0.01	<10	17	82	<10	75	2
8V3551RA/RJ	HL08-55	130336	213.57	215.10	1.53	0.02	1.2	2.76	175	109	<0.5	5	6.39	4	24	31	79	5.38	<1	0.24	<1.0	1.25	2100	<2	0.01	11	1701	4	1.23	<5	6	268	<5	0.01	<10	17	82	<10	72	2
8V3551RA/RJ	HL08-55	130337	215.10	216.40	1.30	0.15	1.1	2.91	693	101	<0.5	5	5.80	16	24	31	87	5.46	<1	0.24	<1.0	2.34	2211	<2	0.01	11	1842	2	0.85	<5	7	218	<5	0.01	<10	17	89	<10	78	2
8V3551RA/RJ	HL08-55	130338	216.40	217.63	1.23	0.02	1.1	2.96	243	95	<0.5	5	5.51	5	23	32	82	5.55	<1	0.24	<1.0	2.48	2132	<2	0.01	11	1753	4	0.85	<5	7	207	<5	0.01	<10	18	89	<10	82	2
8V3551RA/RJ	HL08-55	130339	217.63	218.72	1.09	0.04	1.6	2.30	219	96	<0.5	5	5.98	5	23	28	88	5.01	<1	0.27	<1.0	2.01	2153	<2	0.01	11	1696	7	1.50	<5	6	216	<5	<0.01	<10	17	68	<10	70	2
8V3551RA/RJ	HL08-55	130340	220.09	221.09	1.00	0.04	1.7	2.27	307	118	<0.5	5	7.51	7	28	17	104	5.06	<1	0.31	<1.0	1.73	2780	<2	0.01	16	1250	7	1.77	<5	6	248	<5	<0.01	<10	20	71	<10	98	2
8V3551RA/RJ	HL08-55	130341	221.09	222.60	1.51	0.11	1.3	2.43	250	105	<0.5	6	6.23	6	25	28	71	5.50	<1	0.30	<1.0	1.66	2527	<2	0.01	11	1826	15	1.55	<5	6	226	<5	<0.01	<10	19	63	<10	104	2
8V3551RA/RJ	HL08-55	130342	222.60	224.10	1.50	0.01	0.3	2.56	70	96	<0.5	5	5.96	1	18	34	59	5.21	<1	0.27	<1.0	1.72	2061	<2	0.01	8	1758	3	0.53	<5	6	211	<5	0.01	<10	16	74	<10	80	2
8V3551RA/RJ	HL08-55	130343	224.10	225.60	1.50	0.02	0.5	2.97	147	97	<0.5	5	6.17	3	24	32	60	5.83	<1	0.26	<1.0	2.17	2072	<2	0.01	10	1833	4	0.51	<5	7	268	<5	0.02	<10	17	78	<10	92	2
8V3551RA/RJ	HL08-55	130344	225.60	227.10	1.50	0.01	0.2	2.93	53	113	<0.5	5	5.56	1	20	32	51	5.57	<1	0.32	<1.0	2.02	1908	<2	0.01	9	1863	2	0.30	<5	6	217	<5	0.02	<10	17	78	<10	88	2
8V3551RA/RJ	HL08-55	130345	227.10	228.70	1.60	0.01	0.6	3.07	169	111	<0.5	6	6.12	4	23	44	81	5.57	<1	0.31	<1.0	2.10	2111	<2	0.01	12	1800	3	0.36	<5	6	223	<5	0.02	<10	15	81	<10	90	2
8V3551RA/RJ	HL08-55	130346	228.70	230.20	1.50	0.01	0.6	3.00	116	102	<0.5	7	6.18	2	23	48	76	5.66	<1	0.27	<1.0	2.11	2280	<2	0.01	11	1848	<2	0.36	<5	6	214	<5	0.01	<10	17	82	<10	88	2
8V3551RA/RJ	HL08-55	130347	230.20	230.86	0.66	0.03	1.0	2.50	308	103	<0.5	6	7.49	7	21	34	77	5.04	<1	0.28	<1.0	1.69	2644	<2	0.01	10	1798	6	1.04	<5	6	214	<5	0.02	<10	18	62	<10	71	2
8V3551RA/RJ	HL08-55	130348	230.86	232.30	1.44	0.07	1.6	2.26	691	104	<0.5	5	6.75	18	21	33	88	4.96	<1	0.29	<1.0	1.46	2826	<2	0.01	11	1840	23	1.58	<5	5	208	<5	0.03	<10	15	57	<10	128	2
8V3551RA/RJ	HL08-55	130349	232.30	233.80	1.50	0.08	1.8	2.13	652	119	<0.5	6	6.80	17	20	31	69	4.96	<1	0.35	<1.0	1.30	3119	<2	0.01	8	1687	21	2.04	<5	5	152	<5	0.01	<10	16	59	<10	96	2
8V3551RA/RJ	HL08-55	130350	Blank	Blank		<0.01	2.4	1.12	13	15	<0.5	12	>15.00	<1	1	4	2	0.19	<1	0.04	<1.0	1.76	69	<2	0.03	<1	888	<2	0.15	<5	<1	5809	<5	<0.01	<10	<10	5	<10	1	<1
8V3551RA/RJ	HL08-55	130351	233.80	235.30	1.50	0.24	2.2	1.06	1111	82	<0.5	5	6.84	29	17	30	56	3.9																						

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:				Sb				Cu				Fe				Mn				Ni				P				Pb			
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm				
8V3551RA/RJ	HL08-55	130387	299.50	301.00	1.50	0.04	1.8	2.22	161	157	<0.5	<5	5.73	4	16	4	53	4.63	<1	0.28	<10	1.31	3636	<2	0.02	2	1386	19	1.14	<5	3	181	<5	0.04	<10	19	37	<10	139	1				
8V3551RA/RJ	HL08-55	130388	301.00	302.50	1.50	0.04	1.8	2.22	183	172	<0.5	<5	5.60	5	16	4	58	4.49	<1	0.31	<10	1.25	3769	<2	0.02	2	1349	46	0.88	<5	2	165	<5	0.04	<10	19	37	<10	165	1				
8V3551RA/RJ	HL08-55	130389	302.50	303.96	1.46	0.09	2.0	1.81	165	150	<0.5	<6	6.89	4	16	5	82	4.78	<1	0.27	<10	1.03	4012	<2	0.03	6	1452	37	1.43	<5	2	232	<5	0.01	<10	24	35	<10	176	1				
8V3633RA/RJ	HL08-55	122643	303.96	305.46	1.50	0.02	1.6	2.19	65	210	<0.5	<5	5.33	1	16	8	78	4.66	<1	0.35	<10	1.14	2993	<2	0.03	2	1751	28	1.07	10	3	134	<5	0.02	<10	<10	38	<10	108	2				
8V3633RA/RJ	HL08-55	122644	305.46	306.96	1.50	0.01	1.1	1.94	30	187	<0.5	<5	7.05	<1	12	8	59	3.57	<1	0.34	<10	1.09	2798	<2	0.04	1	1704	31	0.60	8	2	200	<5	0.05	<10	<10	29	<10	89	1				
8V3633RA/RJ	HL08-55	122645	306.96	308.47	1.51	0.01	0.8	2.74	33	162	<0.5	<5	7.90	<1	20	7	4	5.30	<1	0.27	<10	1.93	3900	<2	0.03	2	1439	33	0.64	12	4	243	<5	0.08	<10	<10	50	<10	109	2				
8V3551RA/RJ	HL08-55	130390	308.47	310.15	1.68	0.06	2.2	1.88	95	142	<0.5	<6	7.83	2	15	5	120	4.63	<1	0.25	<10	1.18	3870	<2	0.03	4	1414	13	1.07	<5	3	189	<5	0.01	<10	23	30	<10	122	1				
8V3551RA/RJ	HL08-55	130291	310.15	311.63	1.48	0.05	1.3	1.57	74	161	<0.5	<5	6.66	2	16	5	67	4.04	<1	0.28	<10	0.89	3410	<2	0.03	5	1472	32	0.99	<5	2	176	<5	0.02	<10	19	24	<10	150	1				
8V3551RA/RJ	HL08-55	130392	311.63	313.11	1.48	0.15	2.6	1.53	2397	165	<0.5	<5	4.98	65	15	9	84	4.78	<1	0.30	<10	0.85	3552	<2	0.02	4	1463	519	1.80	<5	2	157	<5	0.02	<10	20	34	11	696	1				
8V3551RA/RJ	HL08-55	130393	313.11	314.61	1.50	0.08	0.8	1.57	749	179	<0.5	<5	5.85	20	12	4	33	3.81	<1	0.32	11	0.79	3285	<2	0.03	2	1474	84	0.61	<5	2	159	<5	0.02	<10	17	22	<10	270	1				
8V3551RA/RJ	HL08-55	130394	314.61	316.10	1.49	0.07	1.3	1.75	314	173	<0.5	<5	4.44	9	12	7	46	5.21	<1	0.32	11	0.85	3089	<2	0.03	2	1226	83	1.55	<5	1	129	<5	0.02	<10	17	23	<10	302	2				
8V3551RA/RJ	HL08-55	130395	316.10	317.60	1.50	0.20	2.4	1.11	1193	165	<0.5	<5	6.33	34	11	8	75	3.67	<1	0.32	<10	0.51	3508	<2	0.02	3	1175	304	1.88	<5	1	188	<5	0.02	<10	18	23	12	716	1				
8V3551RA/RJ	HL08-55	130396	317.60	319.10	1.50	0.02	0.5	1.29	46	205	<0.5	<5	4.57	1	7	6	20	2.93	<1	0.37	14	0.53	2682	<2	0.03	1	1109	75	0.67	<5	1	148	<5	0.01	<10	13	<10	94	1					
8V3551RA/RJ	HL08-55	130397	319.10	320.60	1.50	0.09	0.7	1.20	68	219	<0.5	<5	4.22	2	7	6	26	2.94	<1	0.38	15	0.47	2513	<2	0.03	1	1092	36	0.98	<5	1	145	<5	0.01	<10	<10	13	<10	138	1				
8V3551RA/RJ	HL08-55	130398	320.60	322.10	1.50	0.10	0.4	1.15	1075	206	<0.5	<5	3.73	27	9	6	26	3.10	<1	0.35	13	0.48	2010	<2	0.03	1	1198	13	1.13	<5	1	133	<5	0.01	<10	<10	13	<10	87	1				
8V3551RA/RJ	HL08-55	130399	322.10	323.13	1.03	0.13	0.3	0.93	727	151	<0.5	<5	4.27	18	8	5	14	2.90	<1	0.27	<10	0.46	2220	<2	0.02	1	1176	12	1.25	<5	1	159	<5	0.01	<10	<10	10	<10	65	1				
8V3551RA/RJ	HL08-55	130400	Blank	Blank	<0.01	<0.1	0.09		57	20	<0.5	14	>15.00	2	<1	2	2	0.10	<1	0.04	<10	2.08	65	<2	0.01	<1	89	<2	0.04	<5	<1	4994	<5	<0.01	<10	<10	1	<10	1	<1				
8V3551RA/RJ	HL08-55	130401	323.13	324.18	1.05	0.15	1.0	1.80	1247	167	<0.5	<6	5.58	31	16	7	47	5.05	<1	0.31	<10	1.08	3014	<2	0.02	5	1325	14	1.64	<5	3	203	<5	0.03	<10	13	39	<10	66	2				
8V3551RA/RJ	HL08-55	130402	324.18	325.70	1.52	0.04	1.2	1.90	99	125	<0.5	<6	8.63	2	18	8	50	4.83	<1	0.24	<10	1.27	3389	<2	0.02	6	1101	9	1.53	<5	3	317	<5	0.04	<10	13	55	<10	55	1				
8V3551RA/RJ	HL08-55	130403	325.70	327.20	1.50	0.15	1.3	2.08	98	154	<0.5	<7	6.72	2	24	9	41	5.61	<1	0.29	<10	1.32	2955	<2	0.02	8	1203	22	2.06	<5	4	251	<5	0.06	<10	11	61	<10	81	2				
8V3551RA/RJ	HL08-55	130404	327.20	328.50	1.30	0.05	0.9	2.55	75	127	<0.5	<5	7.44	1	24	16	48	5.74	<1	0.26	<10	1.89	3365	<2	0.02	14	1156	10	1.26	<5	7	260	<5	0.10	<10	13	86	<10	66	2				
8V3551RA/RJ	HL08-55	130405	330.64	332.00	1.36	0.01	1.3	3.11	40	96	<0.5	<5	7.67	1	29	45	97	6.20	<1	0.20	<10	2.72	3006	<2	0.02	27	910	6	0.87	<5	13	288	<5	0.17	<10	<10	138	<10	72	3				
8V3633RA/RJ	HL08-55	122646	332.00	333.50	1.50	0.04	0.8	3.22	67	113	<0.5	<5	8.32	<1	35	49	105	6.00	<1	0.22	<10	2.94	2515	<2	0.03	31	970	31	0.88	15	15	310	<5	0.20	<10	<10	153	<10	81	4				
8V3633RA/RJ	HL08-55	122647	333.50	334.73	1.23	<0.01	0.8	3.51	59	178	<0.5	<5	6.82	<1	39	52	107	6.26	<1	0.24	<10	3.37	2620	<2	0.02	33	1058	31	0.76	15	17	279	<5	0.24	<10	<10	163	<10	82	5				
8V3551RA/RJ	HL08-55	130406	334.73	336.20	1.47	0.04	1.8	3.01	102	116	<0.5	<9	8.89	2	29	39	110	6.53	<1	0.29	<10	2.53	3686	<2	0.03	28	981	6	1.28	<5	11	295	<5	0.04	<10	15	108	<10	72	2				
8V3551RA/RJ	HL08-55	130407	336.20	337.70	1.50	0.01	2.0	3.26	82	103	<0.5	<5	6.36	2	31	43	108	5.82	<1	0.21	<10	2.88	4200	<2	0.02	28	918	5	0.90	<5	14	248	<5	0.17	<10	16	141	<10	75	2				
8V3551RA/RJ	HL08-55	130408	337.70	339.20	1.50	0.10	2.6	3.24	554	118	<0.5	<6	6.27	14	30	34	115	6.26	<1	0.23	<10	2.82	4501	<2	0.02	23	1058	13	1.38	<5	10	216	<5	0.08	<10	16	126	<10	104	2				
8V3551RA/RJ	HL08-55	130409	339.20	340.70	1.50	0.22	1.6	1.81	2813	119	<0.5	<8	5.40	72	18	7	71	4.57	<1	0.25	<10	1.23	3317	<2	0.02	7	1137	37	1.37	<5	3	177	<5	0.01	<10	11	43	<10	360	1				
8V3551RA/RJ	HL08-55	130410	340.70	342.17	1.47	0.06	1.7	1.57	100	118	<0.5	<8	5.01	9	17	7	93	4.61	<1	0.28	<10	0.85	2935	<2	0.03	7	1400	153	1.82	<5	3	145	<5	0.02	<10	10	32	13	761	1				
8V3551RA/RJ	HL08-55	130411	342.17	343.60	1.43	0.04	1.3	1.83	87	148	<0.5	<5	5.12	2	14	8	45	4.75	<1	0.33	<10	0.92	2983	<2	0.03	4	1335	45	1.32	<5	2	148	<5											

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3613RA/RJ	HL08-55	130448	404.00	405.50	1.50	0.11	<0.1	0.43	202	175	<0.5	<5	2.90	5	14	15	17	2.77	<1	0.32	<10	0.23	2124	<2	0.02	<1	971	80	2.29	8	2	114	<5	<0.01	<10	<10	36	<10	106	2
8V3613RA/RJ	HL08-55	130449	405.50	407.00	1.50	0.09	<0.1	0.36	165	138	<0.5	<5	6.60	4	12	7	22	2.22	<1	0.27	<10	0.25	2051	<2	0.03	<1	762	35	1.47	8	2	241	<5	<0.01	<10	<10	29	<10	41	1
8V3613RA/RJ	HL08-55	130450	Blank	Blank		0.01	2.8	0.04	6	11	<0.5	12		<1	1	4	<1	0.04	<1	0.02	<10	1.31	30	<2	<0.01	<1	59	<2	0.08	<5	<1	<5	<0.01	<10	<10	1	<10	1	<1	
8V3613RA/RJ	HL08-55	130451	407.00	408.50	1.50	0.16	<0.1	0.46	230	176	<0.5	<5	4.30	6	16	10	17	3.80	<1	0.31	<10	0.49	1803	<2	0.04	<1	1019	48	2.79	10	2	204	<5	<0.01	<10	<10	58	<10	118	3
8V3613RA/RJ	HL08-55	130452	408.50	409.52	1.02	0.06	<0.1	0.90	80	132	<0.5	<5	5.64	2	9	7	10	3.41	<1	0.23	<10	0.65	1932	<2	0.03	<1	931	54	1.34	8	2	215	<5	<0.01	<10	<10	68	<10	90	2
8V3613RA/RJ	HL08-55	130453	409.52	410.75	1.23	0.03	<0.1	1.46	64	128	<0.5	<5	4.55	4	13	2	48	4.11	<1	0.23	<10	0.87	1790	<2	0.03	<1	1148	298	1.49	9	2	184	<5	<0.01	<10	<10	82	<10	351	3
8V3613RA/RJ	HL08-55	130454	410.75	411.85	1.10	0.02	<0.1	1.63	35	149	<0.5	<5	5.28	<1	15	8	23	4.16	<1	0.26	<10	0.86	1703	4	<0.01	<1	1282	22	1.17	13	2	206	<5	<0.01	<10	<10	82	<10	48	3
8V3613RA/RJ	HL08-55	130455	411.85	413.37	1.52	0.05	<0.1	1.55	91	145	<0.5	<5	3.91	2	16	2	34	4.40	<1	0.27	<10	0.83	1299	<2	0.04	<1	1237	21	1.83	8	2	140	<5	0.01	<10	<10	77	<10	82	3
8V3613RA/RJ	HL08-55	130456	413.37	414.87	1.50	0.03	<0.1	1.59	67	150	<0.5	<5	4.81	1	16	3	31	4.01	<1	0.28	<10	0.87	1887	<2	0.03	<1	1171	25	1.32	8	3	202	<5	0.01	<10	<10	83	<10	99	3
8V3613RA/RJ	HL08-55	130457	414.87	416.30	1.43	0.01	<0.1	2.09	32	150	<0.5	<5	3.36	<1	17	<1	30	4.67	<1	0.25	<10	1.21	1632	<2	0.03	<1	1264	22	0.90	9	3	140	<5	0.01	<10	<10	99	<10	77	4
8V3613RA/RJ	HL08-55	130458	416.30	417.80	1.50	0.02	<0.1	2.07	31	147	<0.5	<5	3.61	<1	18	<1	34	4.90	<1	0.26	<10	1.09	1633	<2	0.04	<1	1309	35	1.17	10	3	139	<5	0.01	<10	<10	95	<10	166	3
8V3613RA/RJ	HL08-55	130459	417.80	419.30	1.50	0.05	<0.1	1.71	70	136	<0.5	<5	3.88	2	17	<1	37	4.43	<1	0.24	<10	0.99	1732	<2	0.03	<1	1262	24	1.51	9	3	149	<5	0.01	<10	<10	85	<10	196	3
8V3613RA/RJ	HL08-55	130460	419.30	420.80	1.50	0.03	<0.1	1.89	70	145	<0.5	<5	3.49	5	17	<1	34	4.99	<1	0.26	<10	1.02	1966	<2	0.03	<1	1320	58	1.65	9	3	125	<5	0.01	<10	<10	89	13	864	3
8V3613RA/RJ	HL08-55	130461	420.80	422.30	1.50	0.02	<0.1	2.06	82	160	<0.5	<5	3.92	2	18	<1	39	4.91	<1	0.28	<10	1.12	2237	<2	0.04	<1	1402	50	1.17	8	3	133	<5	0.01	<10	<10	95	<10	338	3
8V3613RA/RJ	HL08-55	130462	422.30	423.80	1.50	0.02	<0.1	2.41	51	205	<0.5	<5	5.03	1	19	<1	41	4.96	<1	0.38	<10	1.25	2330	<2	0.05	<1	1396	31	0.88	10	4	171	<5	0.01	<10	<10	105	<10	125	3
8V3613RA/RJ	HL08-55	130463	423.80	425.30	1.50	0.09	<0.1	2.06	44	185	<0.5	<5	4.90	2	17	<1	75	4.44	<1	0.34	<10	1.08	2366	<2	0.03	<1	1403	213	1.02	10	3	164	<5	0.01	<10	<10	92	<10	271	3
8V3613RA/RJ	HL08-55	130464	425.30	426.80	1.50	0.04	<0.1	1.97	53	187	<0.5	<5	4.53	1	15	<1	48	4.58	<1	0.33	<10	1.00	2305	<2	0.04	<1	1318	30	1.28	10	3	154	<5	0.01	<10	<10	95	<10	263	3
8V3613RA/RJ	HL08-55	130465	426.80	428.30	1.50	0.03	<0.1	2.25	37	186	<0.5	<5	4.40	1	16	<1	36	4.71	<1	0.35	<10	1.10	2045	<2	0.02	<1	1329	33	0.79	9	4	153	<5	0.01	<10	<10	94	<10	183	3
8V3613RA/RJ	HL08-55	130466	428.30	429.80	1.50	0.01	<0.1	2.35	24	183	<0.5	<5	5.64	<1	19	<1	49	5.04	<1	0.32	<10	1.06	2013	<2	<0.01	<1	1334	27	0.70	10	4	199	<5	0.01	<10	<10	104	<10	53	3
8V3613RA/RJ	HL08-55	130467	429.80	431.30	1.50	0.01	<0.1	2.35	22	168	<0.5	<5	4.70	<1	15	2	61	4.92	<1	0.32	<10	1.06	1578	<2	<0.01	<1	1360	26	0.70	10	4	179	<5	0.01	<10	<10	99	<10	41	3
8V3613RA/RJ	HL08-55	130468	431.30	432.80	1.50	0.01	<0.1	1.99	20	175	<0.5	<5	4.62	<1	13	2	38	4.27	<1	0.32	<10	0.97	1369	<2	<0.01	<1	1298	21	0.58	8	4	167	<5	0.01	<10	<10	85	<10	30	3
8V3613RA/RJ	HL08-55	130469	432.80	434.30	1.50	0.02	<0.1	1.51	42	182	<0.5	<5	4.60	<1	20	5	22	4.81	<1	0.33	<10	0.88	1524	<2	<0.01	<1	1345	26	2.18	9	4	151	<5	<0.01	<10	<10	84	<10	25	3
8V3613RA/RJ	HL08-55	130470	434.30	435.23	0.93	0.02	<0.1	1.09	28	105	<0.5	<5	2.97	<1	11	11	42	5.00	<1	0.39	<10	0.69	1259	<2	<0.01	<1	1370	17	3.50	9	3	123	<5	<0.01	<10	<10	70	<10	21	3
8V3613RA/RJ	HL08-55	130471	435.23	435.99	0.76	0.01	<0.1	0.72	17	58	<0.5	<5	1.19	<1	19	16	34	5.44	<1	0.44	<10	0.36	510	<2	<0.01	<1	1348	22	>5.00	10	3	54	<5	<0.01	<10	<10	74	<10	19	4
8V3613RA/RJ	HL08-55	130472	435.99	437.56	1.57	0.05	<0.1	0.40	54	117	<0.5	<5	6.02	2	15	20	34	4.02	<1	0.29	<10	0.26	2163	<2	0.03	<1	931	125	3.71	11	3	456	<5	<0.01	<10	<10	55	<10	207	3
8V3613RA/RJ	HL08-55	130473	437.56	439.00	1.44	0.05	<0.1	1.17	51	214	<0.5	<5	2.94	1	18	7	53	5.01	<1	0.44	<10	0.79	1424	<2	0.03	<1	1434	38	1.80	13	3	139	<5	<0.01	<10	<10	80	<10	115	3
8V3613RA/RJ	HL08-55	130474	439.00	440.50	1.50	0.02	<0.1	1.79	54	200	<0.5	<5	4.29	1	39	2	56	5.21	<1	0.34	<10	0.86	1896	<2	0.04	<1	1305	39	2.05	19	3	133	<5	0.01	<10	<10	99	<10	144	4
8V3613RA/RJ	HL08-55	130475	Std	PM1116		0.13	806.0	0.63	524	174	<0.5	35	0.50	21	7	24	7438	2.09	5	0.17	<10	0.55	268	524	0.04	<1	243	836	1.05	1776	2	80	<5	0.06	<10	<10	<1	<10	866	3
8V3613RA/RJ	HL08-55	130476	440.50	442.00	1.50	0.02	<0.1	2.03	38	209	<0.5	<5	4.54	1	28	<1	71	5.04	<1	0.35	<10	0.88	2125	2	0.02	<1	1317	34	1.21	17	3	145	<5	0.02	<10	<10	95	<10	121	4
8V3613RA/RJ	HL08-55	130477	442.00	443.50	1.50	0.27	<0.1	2.09	49	212	<0.5	<5	5.31	2	22	<1	57	5.04	<																					

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3551RA/RJ	HL08-56	121626	56.19	58.00	1.81	0.01	<0.1	1.95	<5	554	<0.5	<5	3.01	<1	16	56	17	4.02	<1	0.16	28	1.48	720	<2	0.04	13	2062	7	0.07	<5	5	132	<5	0.01	<10	<10	51	<10	109	4
8V3551RA/RJ	HL08-56	121627	58.00	59.81	1.81	0.01	<0.1	1.91	<5	726	<0.5	<5	2.79	<1	21	53	7	3.96	<1	0.15	27	1.51	724	<2	0.05	12	1979	6	0.03	<5	6	80	<5	0.28	<10	<10	72	<10	105	13
8V3551RA/RJ	HL08-56	121628	59.81	61.55	1.74	0.43	0.7	2.03	51	65	<0.5	<5	8.47	1	22	75	134	4.37	<1	0.18	<10	1.13	1693	2	0.05	13	1126	6	0.58	<5	9	199	<5	0.10	<10	<10	120	<10	78	6
8V3551RA/RJ	HL08-56	121629	61.55	63.30	1.75	0.02	0.9	3.51	45	104	<0.5	<5	4.01	1	39	155	120	7.31	<1	0.21	<10	2.61	1673	<2	0.03	32	1886	14	0.61	<5	23	153	<5	0.17	<10	<10	235	<10	119	6
8V3551RA/RJ	HL08-56	121630	63.30	65.04	1.74	0.02	0.4	3.74	31	117	<0.5	<5	6.38	<1	39	162	106	6.64	1	0.23	<10	3.29	2007	<2	0.03	28	1777	10	0.33	<5	25	216	<5	0.15	<10	11	243	<10	94	6
8V3551RA/RJ	HL08-56	121631	65.04	66.05	1.01	0.01	<0.1	0.44	9	45	<0.5	<5	1.65	<1	7	54	20	1.49	<1	0.22	11	0.42	575	2	0.05	5	241	25	0.10	<5	3	101	10	<0.01	<10	<10	23	<10	32	9
8V3551RA/RJ	HL08-56	121632	74.70	75.65	0.95	0.01	<0.1	0.26	<5	25	<0.5	<5	0.54	<1	1	53	1	0.46	<1	0.22	13	0.04	281	<2	0.06	2	28	23	0.03	<5	1	16	13	<0.01	<10	<10	2	<10	14	7
8V3551RA/RJ	HL08-56	121633	75.65	76.25	0.60	0.02	<0.1	1.51	<5	164	0.8	5	2.80	<1	18	69	15	4.46	<1	0.26	28	1.68	834	<2	0.04	16	2464	12	0.15	<5	6	175	<5	<0.01	<10	<10	54	<10	127	4
8V3551RA/RJ	HL08-56	121634	76.25	77.40	1.15	0.01	<0.1	0.26	<5	34	<0.5	<5	0.32	<1	1	88	2	0.47	<1	0.22	11	0.08	155	<2	0.05	3	77	14	0.04	<5	<1	23	11	<0.01	<10	<10	2	<10	8	6
8V3551RA/RJ	HL08-56	121635	79.80	81.80	2.00	0.03	0.3	3.30	22	262	<0.5	7	6.55	1	32	136	93	6.34	1	0.45	<10	3.06	2009	<2	0.04	24	1750	30	0.43	<5	21	249	<5	0.05	<10	12	205	<10	141	4
8V3551RA/RJ	HL08-56	121636	81.80	83.80	2.00	0.01	0.4	3.03	31	66	<0.5	7	6.17	<1	32	137	65	5.97	<1	0.20	<10	2.67	1637	<2	0.01	26	1675	20	0.57	<5	17	171	<5	0.01	<10	<10	186	<10	78	3
8V3551RA/RJ	HL08-56	121637	83.80	85.80	2.00	0.03	0.5	3.07	34	77	<0.5	8	4.76	<1	35	135	84	6.39	<1	0.24	<10	2.46	1555	<2	0.01	29	1796	24	0.70	<5	15	151	<5	0.01	<10	<10	177	<10	90	3
8V3551RA/RJ	HL08-56	121638	85.80	87.25	1.45	0.06	0.9	3.24	38	49	<0.5	8	4.28	1	33	129	103	6.71	<1	0.18	<10	2.79	1586	<2	0.01	27	1661	22	0.77	<5	15	189	<5	0.01	<10	13	167	<10	109	3
8V3551RA/RJ	HL08-56	121639	87.25	89.25	2.00	0.03	1.1	3.78	38	40	<0.5	7	7.87	<1	29	126	83	7.03	<1	0.19	<10	3.71	2157	<2	0.01	24	1684	20	0.71	<5	14	247	<5	0.02	<10	17	174	<10	80	4
8V3551RA/RJ	HL08-56	121640	89.25	91.25	2.00	0.31	1.1	3.00	1343	55	<0.5	7	7.73	32	34	129	70	6.37	<1	0.31	<10	2.49	2096	<2	0.01	26	1815	32	1.39	<5	12	244	<5	0.01	<10	16	145	<10	82	3
8V3551RA/RJ	HL08-56	121641	91.25	93.25	2.00	0.05	1.6	3.13	192	61	<0.5	<5	8.31	4	42	142	86	6.28	<1	0.29	<10	2.60	2022	<2	0.01	31	1839	19	0.83	<5	15	274	<5	0.05	<10	14	160	<10	80	4
8V3551RA/RJ	HL08-56	121642	93.25	95.25	2.00	0.19	1.5	3.01	1143	85	<0.5	5	8.30	27	37	116	57	6.00	<1	0.30	<10	2.43	2069	<2	0.01	27	1701	17	0.85	<5	12	235	<5	0.04	<10	15	142	<10	76	3
8V3551RA/RJ	HL08-56	121643	95.25	97.25	2.00	0.06	1.8	3.15	446	58	<0.5	<5	7.94	10	32	121	85	6.35	1	0.26	<10	2.56	2075	<2	0.01	24	1719	15	0.76	<5	15	250	<5	0.06	<10	14	168	<10	86	3
8V3551RA/RJ	HL08-56	121644	97.25	99.25	2.00	0.01	0.8	3.49	84	108	<0.5	6	7.36	2	32	135	61	6.45	1	0.21	<10	3.24	1847	<2	0.01	26	1649	15	0.42	<5	16	238	<5	0.02	<10	13	190	<10	105	3
8V3551RA/RJ	HL08-56	121645	99.25	101.25	2.00	0.03	1.3	3.45	71	662	<0.5	6	5.49	1	36	108	96	6.60	1	0.25	<10	3.01	1819	<2	0.01	26	1807	30	0.58	<5	13	186	<5	0.01	<10	13	162	<10	136	3
8V3551RA/RJ	HL08-56	121646	101.25	103.25	2.00	0.03	1.2	3.20	166	65	<0.5	7	7.70	3	35	125	89	6.46	1	0.22	<10	2.87	2454	<2	0.01	26	1795	22	0.61	<5	14	192	<5	0.01	<10	14	173	<10	112	3
8V3551RA/RJ	HL08-56	121647	103.25	105.25	2.00	0.05	1.3	1.79	41	110	<0.5	<5	4.97	2	16	29	97	4.34	<1	0.39	<10	1.08	1688	2	0.01	7	1453	31	0.64	<5	4	133	<5	<0.01	<10	<10	55	<10	104	2
8V3551RA/RJ	HL08-56	121648	105.25	107.25	2.00	0.08	1.1	1.86	152	83	<0.5	<5	7.91	5	16	32	78	3.82	<1	0.37	<10	1.14	1981	<2	0.01	7	1288	19	0.29	<5	5	215	<5	0.01	<10	11	60	<10	103	2
8V3551RA/RJ	HL08-56	121649	107.25	108.54	1.29	0.02	1.1	2.13	43	95	<0.5	<5	8.16	4	20	29	65	4.37	<1	0.40	10	1.22	2036	2	0.01	8	1495	32	0.45	<5	6	215	<5	0.04	<10	12	67	<10	151	2
8V3551RA/RJ	HL08-56	121650	Blank	Blank	0.01	<0.1	0.12	<5	11	<0.5	10	>15.00	<1	1	4	1	0.16	1	0.05	<10	1.99	142	<2	0.01	1	114	<2	0.03	<5	<1	5426	<5	<0.01	<10	<10	5	<10	1	<1	
8V3551RA/RJ	HL08-56	121651	108.54	109.80	1.26	0.03	1.6	2.74	51	102	<0.5	<5	3.84	2	25	44	76	5.99	<1	0.41	<10	1.75	1952	2	0.01	12	1759	41	1.12	<5	6	123	<5	0.03	<10	14	96	<10	157	3
8V3551RA/RJ	HL08-56	121652	109.80	111.30	1.50	0.16	2.9	2.31	195	106	<0.5	<5	5.42	5	22	29	126	5.10	<1	0.45	<10	1.31	2186	5	0.01	9	1668	33	1.10	<5	5	157	<5	0.03	<10	14	74	<10	121	2
8V3551RA/RJ	HL08-56	121653	111.30	113.30	2.00	0.14	5.7	2.01	425	116	<0.5	<5	6.07	10	17	19	169	4.99	<1	0.47	<10	0.93	2161	10	0.01	3	1541	45	1.58	<5	3	188	<5	0.03	<10	16	51	<10	128	2
8V3551RA/RJ	HL08-56	121654	113.30	114.70	1.40	0.11	3.2	2.02	331	122	<0.5	<5	6.74	9	18	9	85	5.04	<1	0.50	<10	0.92	2320	10	0.01	4	1579	51	1.67	<5	3	209	<5	0.03	<10	16	46	<10	158	2
8V3551RA/RJ	HL08-56	121655	114.70	115.90	1.20	0.08	2.1	1.99	62	96	<0.5	<5	7.89	2	10	22	48	4.15	<1	0.39	10	1.07	2463	12	0.01	3	1355	22	0.48	<5	3	201	<5	0.03	<10	15	41	<10	126	2
8V3551RA/RJ	HL08-56	121656	115.90	117.09	1.19	0.26	2.4	1.73	578	91	<0.5	<5	8.60	14	13	14	92	4.66	<1	0.39	10	0.80	2476	2	0.01	3	1080	34	1.67	<5	3	179	<5	0.03	<10	16	46	<10	121	2
8V3551RA/RJ	HL08-56	121657	117.09	119.00	1.91	0.13	3.1	2.59	157	103	<0.5	<5	6.06	5	21	10	294	6.66	<1	0.36	10	1.41	2681	<2	0.02	4	1455	27	1.57	<5	4	169	<5	0.08	<10	21	83	<10	183	3
8V3551RA/RJ	HL08-56	121658	119.00	121.00	2.00	0.11	2.6	1.54	46	114	<0.5	<5	7.35	5	14	10	229	3.53	<1	0.38	10	0.64	1911	5	0.02	2	1287	57	0.57	<5	3	187	<5	0.05	<10	10	39	<10	348	5
8V3551RA/RJ	HL08-56	121659	121.00	122.74	1.74	0.11	2.3	2.11	35	144	<0.5	<5	4.27	4	19	9	258	5.45	<1	0.47																				

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm	
8V3551RA/RJ	HL08-56	121698	191.00	192.20	1.20	0.02	0.7	2.19	96	141	<0.5	<5	4.03	3	18	6	43	4.96	<1	0.47	13	1.07	1813	<2	0.02	3	1698	45	1.09	<5	2	111	<5	0.08	<10	<10	42	<10	84	2	
8V3551RA/RJ	HL08-56	121699	192.20	193.40	1.20	0.02	0.4	2.15	101	159	<0.5	<5	7.93	4	19	8	32	4.91	<1	0.53	10	0.96	2377	4	0.02	4	1669	34	1.01	<5	3	229	<5	0.09	<10	<10	51	<10	121	2	
8V3551RA/RJ	HL08-56	121700	Blank	Blank		0.01	<0.1	0.10	<5	13	<0.5	10	>15.00	<1	1	1	<1	0.08	<1	0.05	<10	1.62	55	<2	0.01	<1	663	<2	0.12	<5	<1	5854	<5	<0.01	<10	<10	2	<10	2	<1	
8V3551RA/RJ	HL08-56	121701	193.40	194.97	1.57	0.03	0.6	1.93	210	137	<0.5	<5	9.28	7	16	6	39	4.40	<1	0.47	10	0.88	2444	<2	0.02	2	1586	36	0.87	<5	2	256	<5	0.04	<10	<10	15	<10	106	2	
8V3551RA/RJ	HL08-56	121702	194.97	196.56	1.59	0.03	1.0	2.16	148	360	<0.5	<6	7.32	13	16	13	32	5.32	<1	0.47	10	1.00	2772	2	0.02	3	1636	133	1.29	<5	2	257	<5	<0.01	<10	<10	51	46	15	874	2
8V3551RA/RJ	HL08-56	121703	196.56	198.11	1.55	0.04	0.3	1.90	134	124	<0.5	<5	7.08	4	12	26	17	4.48	<1	0.45	<10	0.85	2443	2	0.02	4	1485	41	1.04	<5	2	194	<5	<0.01	<10	<10	16	39	<10	135	2
8V3551RA/RJ	HL08-56	121704	198.11	200.00	1.89	0.05	1.1	1.99	638	125	<0.5	<6	6.05	16	18	12	37	5.67	<1	0.46	<10	0.90	2432	<2	0.02	4	1785	33	2.21	<5	3	193	<5	<0.01	<10	<10	15	49	<10	156	2
8V3551RA/RJ	HL08-56	121705	200.00	200.70	0.70	0.05	0.9	1.78	523	119	<0.5	<5	6.35	13	15	5	37	4.47	<1	0.46	<10	0.72	2244	<2	0.01	3	1514	26	1.45	<5	2	250	<5	<0.01	<10	<10	16	39	<10	108	2
8V3551RA/RJ	HL08-56	121706	200.70	202.00	1.30	0.04	2.1	2.35	361	159	<0.5	<6	4.77	9	26	3	86	6.67	<1	0.44	<10	1.15	2273	<2	0.02	5	1666	59	2.41	<5	3	209	<5	<0.01	<10	<10	21	72	<10	145	3
8V3551RA/RJ	HL08-56	121707	202.00	204.00	2.00	0.98	3.3	1.74	1555	119	<0.5	<7	8.56	38	25	5	64	6.02	<1	0.46	<10	0.78	2661	<2	0.01	5	1429	34	3.81	<5	3	251	<5	<0.01	<10	<10	21	63	<10	131	3
8V3551RA/RJ	HL08-56	121708	204.00	206.00	2.00	0.82	5.0	1.86	1171	119	<0.5	<7	7.46	30	20	3	47	5.68	<1	0.42	<10	0.85	2292	<2	0.02	4	1694	101	2.67	<5	3	242	<5	<0.01	<10	<10	18	65	<10	197	2
8V3551RA/RJ	HL08-56	121709	206.00	208.00	2.00	0.03	0.9	2.01	276	139	<0.5	<6	7.11	7	24	5	59	5.86	<1	0.44	<10	1.02	2321	<2	0.02	5	1666	15	2.69	<5	4	247	<5	0.01	<10	<10	18	72	<10	106	2
8V3551RA/RJ	HL08-56	121710	208.00	210.00	2.00	0.05	1.3	2.76	387	108	<0.5	<9	5.88	9	27	5	53	8.89	<1	0.41	<10	1.51	2755	<2	0.02	6	1747	37	4.39	<5	5	179	<5	0.01	<10	<10	25	98	<10	120	4
8V3551RA/RJ	HL08-56	121711	210.00	212.00	2.00	0.02	2.8	1.64	5795	126	<0.5	<7	8.09	143	19	8	39	6.42	<1	0.44	<10	0.76	2912	<2	0.01	4	1258	77	4.02	27	3	315	<5	<0.01	<10	<10	25	48	<10	134	2
8V3551RA/RJ	HL08-56	121712	212.00	212.50	0.50	0.40	0.9	2.32	97	160	<0.5	<6	4.44	3	24	4	50	6.01	<1	0.47	<10	1.25	2437	<2	0.02	6	1874	16	2.15	<5	4	148	<5	0.01	<10	<10	13	75	<10	188	3
8V3551RA/RJ	HL08-56	121713	212.50	214.50	2.00	0.08	0.2	2.37	50	227	<0.5	<6	3.41	2	22	6	38	6.15	<1	0.43	<10	1.14	2376	<2	0.02	4	1708	26	1.12	<5	4	148	<5	<0.01	<10	<10	18	68	<10	167	3
8V3551RA/RJ	HL08-56	121714	214.50	216.50	2.00	0.05	0.4	2.37	51	189	<0.5	<6	5.03	3	25	3	27	5.46	<1	0.44	<10	1.44	2714	<2	0.02	5	1673	111	0.83	<5	4	273	<5	<0.01	<10	<10	20	46	<10	284	2
8V3551RA/RJ	HL08-56	121715	216.50	218.50	2.00	0.04	1.0	2.67	111	366	<0.5	<6	5.99	3	23	62	47	5.59	<1	0.31	<10	2.13	2623	<2	0.01	14	1559	84	1.08	<5	7	267	<5	<0.01	<10	<10	19	109	<10	176	2
8V3551RA/RJ	HL08-56	121716	218.50	220.50	2.00	0.03	1.3	2.56	243	207	<0.5	<6	7.21	6	28	68	67	6.00	<1	0.13	<10	2.19	2084	<2	0.02	15	1713	24	1.76	<5	15	230	<5	0.02	<10	<10	13	219	<10	119	3
8V3551RA/RJ	HL08-56	121717	220.50	222.50	2.00	0.04	1.9	2.42	213	87	<0.5	<5	5.89	5	28	47	87	6.01	<1	0.17	<10	2.09	1884	<2	0.02	13	1799	31	2.24	<5	12	170	<5	0.06	<10	<10	11	190	<10	161	3
8V3551RA/RJ	HL08-56	121718	222.50	224.50	2.00	0.03	2.4	2.39	255	80	<0.5	<6	6.42	5	29	49	90	6.55	<1	0.17	<10	2.10	1762	<2	0.01	15	1856	19	2.19	<5	12	198	<5	0.02	<10	<10	182	<10	96	3	
8V3613RA/RJ	HL08-56	121719	224.50	226.50	2.00	0.04	1.0	2.38	185	80	<0.5	<7	6.53	4	27	51	82	6.41	<1	0.21	<10	1.96	1814	<2	0.01	14	1766	26	1.91	<5	10	233	<5	0.01	<10	<10	139	<10	116	3	
8V3613RA/RJ	HL08-56	121720	226.50	228.50	2.00	0.08	0.4	3.04	86	55	<0.5	<7	8.82	4	34	102	97	7.34	<1	0.11	<10	2.54	2102	<2	0.01	21	1656	19	0.91	<5	18	305	<5	0.01	<10	<10	219	<10	132	3	
8V3613RA/RJ	HL08-56	121721	228.50	230.49	1.99	0.02	0.2	3.43	84	44	<0.5	<5	8.93	11	35	106	96	7.82	<1	0.05	<10	3.12	2136	<2	0.01	21	1723	39	0.63	<5	25	331	<5	0.04	<10	<10	283	<10	152	4	
8V3613RA/RJ	HL08-56	121722	230.49	232.50	2.01	0.01	<0.1	3.89	68	59	<0.5	<5	5.84	1	35	97	83	8.14	<1	0.04	<10	4.37	1645	<2	0.01	20	1735	12	0.60	<5	28	238	<5	0.12	<10	<10	287	<10	103	5	
8V3613RA/RJ	HL08-56	121723	232.50	234.50	2.00	0.02	0.1	3.00	65	45	<0.5	<5	7.99	5	35	118	88	7.01	<1	0.04	<10	3.22	1880	<2	0.02	21	1767	28	0.62	<5	19	291	<5	0.14	<10	<10	260	<10	114	5	
8V3613RA/RJ	HL08-56	121724	234.50	236.50	2.00	0.01	0.2	2.97	78	63	<0.5	<5	6.09	3	36	125	72	7.05	<1	0.04	<10	3.39	1843	<2	0.02	22	1787	24	0.80	<5	17	236	<5	0.14	<10	<10	241	<10	177	5	
8V3613RA/RJ	HL08-56	121725	Std	PM 92.52		6.63	2.6	1.50	769	146	<0.5	<183	8.91	16	48	73	484	6.48	15	0.19	12	0.38	894	152	0.04	74	1018	87	2.17	<5	3	118	<5	0.11	<10	<10	41	53	92	17	
8V3613RA/RJ	HL08-56	121726	236.50	238.50	2.00	0.01	0.1	3.29	19	50	<0.5	<5	7.63	<1	35	255	121	6.50	<1	0.03	<10	3.92	2105	<2	0.01	34	1781	11	0.24	<5	17	327	<5	0.12	<10	<10	231	<10	83	5	
8V3613RA/RJ	HL08-56	121727	238.50	240.50	2.00	0.01	0.3	2.29																																	

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm	
8V3613RA/RJ	HLO8-57	121769	93.50	95.50	2.00	0.01	<0.1	2.32	69	64	<0.5	<5	5.30	2	34	233	95	5.83	<1	0.17	<10	2.39	1379	<2	0.04	29	1652	40	1.09	13	12	145	<5	0.04	<10	<10	289	<10	106	5	
8V3613RA/RJ	HLO8-57	121770	95.50	97.50	2.00	0.03	<0.1	2.30	33	47	<0.5	<5	4.59	<1	28	159	89	5.64	<1	0.17	<10	2.44	1347	<2	0.04	19	1681	51	0.86	13	10	121	<5	0.06	<10	<10	252	<10	69	5	
8V3613RA/RJ	HLO8-57	121771	97.50	99.50	2.00	0.04	<0.1	2.27	45	59	<0.5	<5	6.91	1	25	168	76	5.48	<1	0.14	<10	2.52	1511	<2	0.04	18	1364	44	0.80	11	11	163	<5	0.03	<10	<10	247	<10	75	4	
8V3613RA/RJ	HLO8-57	121772	99.50	101.50	2.00	0.06	<0.1	2.17	66	58	<0.5	<5	6.56	1	26	161	93	5.35	<1	0.18	<10	2.13	1708	<2	0.04	18	1443	43	0.95	13	9	154	<5	0.04	<10	<10	213	<10	79	4	
8V3613RA/RJ	HLO8-57	121773	101.50	103.50	2.00	0.03	<0.1	2.82	26	120	<0.5	<5	5.97	<1	32	197	93	6.26	<1	0.14	<10	3.03	1596	<2	0.05	24	1578	48	0.55	15	14	164	<5	0.06	<10	<10	232	<10	112	5	
8V3613RA/RJ	HLO8-57	121774	103.50	105.49	1.99	0.03	<0.1	3.06	24	51	<0.5	<5	6.11	1	35	226	92	6.57	<1	0.12	<10	3.40	1555	<2	0.03	25	1628	44	0.43	15	18	172	<5	0.10	<10	<10	336	<10	143	5	
8V3613RA/RJ	HLO8-57	121775	Std	PM1110			1.84	186.0	0.65	204	194	<0.5	<49	6.01	7	16	39	3509	3.18	3	0.15	<10	0.20	562	69	0.04	35	537	204	1.23	250	2	154	<5	0.07	<10	18	57	25	242	12
8V3613RA/RJ	HLO8-57	121776	105.49	107.50	2.01	0.01	<0.1	3.03	21	73	<0.5	<5	6.51	<1	34	283	96	6.57	<1	0.12	<10	3.66	1510	<2	0.04	27	1937	51	0.54	17	18	157	<5	0.14	<10	<10	358	<10	100	6	
8V3613RA/RJ	HLO8-57	121777	107.50	109.50	2.00	0.03	<0.1	2.58	29	53	<0.5	<5	11.28	<1	30	204	93	5.89	<1	0.13	<10	2.86	1993	<2	0.03	24	1583	41	0.59	13	14	207	<5	0.09	<10	<10	301	<10	60	4	
8V3613RA/RJ	HLO8-57	121778	109.50	111.50	2.00	0.07	<0.1	2.49	69	62	<0.5	<5	7.97	1	32	179	93	5.99	<1	0.19	<10	2.50	1556	<2	0.02	23	1726	47	1.08	15	12	193	<5	0.08	<10	<10	266	<10	61	5	
8V3613RA/RJ	HLO8-57	121779	111.50	113.50	2.00	0.07	<0.1	2.32	50	48	<0.5	<5	7.39	1	29	173	77	5.50	<1	0.19	<10	2.29	1438	<2	0.03	23	1561	40	0.85	14	11	165	<5	0.10	<10	<10	230	<10	60	5	
8V3613RA/RJ	HLO8-57	121780	113.50	115.50	2.00	0.03	<0.1	2.46	36	61	<0.5	<5	6.31	<1	31	191	98	5.90	<1	0.23	<10	2.20	1430	<2	0.03	23	1876	46	0.89	16	11	162	<5	0.11	<10	<10	247	<10	89	5	
8V3613RA/RJ	HLO8-57	121781	115.50	117.50	2.00	0.04	<0.1	2.24	42	52	<0.5	<5	8.14	1	25	151	72	5.06	<1	0.17	<10	2.14	1858	<2	0.03	16	1495	37	0.53	13	10	187	<5	0.09	<10	<10	219	<10	78	4	
8V3613RA/RJ	HLO8-57	121782	117.50	118.06	0.56	0.02	<0.1	2.24	46	69	<0.5	<5	5.57	1	26	82	76	3.4	<1	0.22	<10	1.96	1573	<2	0.03	10	1590	37	0.73	12	6	119	<5	0.11	<10	<10	176	<10	79	5	
8V3613RA/RJ	HLO8-57	121783	118.06	118.65	0.59	<0.01	<0.1	1.66	18	121	<0.5	<5	2.94	<1	26	109	22	4.21	<1	0.08	15	1.80	689	<2	0.10	14	2412	23	0.07	16	6	81	<5	0.41	<10	43	161	<10	122	21	
8V3613RA/RJ	HLO8-57	121784	118.65	120.65	2.00	0.02	0.6	2.57	34	64	<0.5	<9	5.85	1	23	52	92	5.28	1	0.21	<10	1.73	1997	<2	0.01	14	1552	19	0.65	<5	6	159	<5	0.04	<10	<10	83	<10	73	3	
8V3613RA/RJ	HLO8-57	121785	120.65	122.65	2.00	0.04	0.9	2.76	53	250	<0.5	<9	3.63	1	26	95	106	5.83	1	0.27	<10	1.91	1944	<2	0.01	21	1663	22	0.75	<5	9	107	<5	0.03	<10	<10	117	<10	92	3	
8V3613RA/RJ	HLO8-57	121786	122.65	124.65	2.00	0.07	0.8	2.35	59	192	<0.5	<11	5.11	2	19	40	72	5.80	3	0.35	<10	1.31	2019	7	0.01	10	1700	30	1.19	<5	5	138	<5	0.02	<10	14	76	<10	123	2	
8V3613RA/RJ	HLO8-57	121787	124.65	126.65	2.00	0.03	0.2	2.32	23	81	<0.5	<11	5.16	1	15	7	38	5.21	1	0.31	<10	1.33	2014	2	0.01	4	1466	19	0.73	<5	3	176	<5	0.02	<10	<10	61	<10	98	2	
8V3613RA/RJ	HLO8-57	121788	126.65	128.65	2.00	0.20	0.5	2.08	32	84	<0.5	<7	3.96	1	16	8	53	5.01	1	0.28	<10	1.04	1768	2	0.02	3	1485	32	0.92	<5	3	171	<5	0.02	<10	<10	60	<10	109	2	
8V3613RA/RJ	HLO8-57	121789	128.65	130.65	2.00	0.03	<0.1	1.48	11	82	<0.5	<5	4.46	1	9	16	28	3.43	<1	0.22	<10	1.73	1537	<2	0.02	1	1274	10	0.37	<5	3	134	<5	0.05	<10	<10	42	<10	75	2	
8V3613RA/RJ	HLO8-57	121790	130.65	132.65	2.00	0.02	<0.1	1.61	13	97	<0.5	<5	3.75	<1	10	14	30	3.68	<1	0.30	<10	0.77	1427	<2	0.02	1	1352	19	0.54	<5	3	129	<5	0.08	<10	<10	42	<10	70	3	
8V3613RA/RJ	HLO8-57	121791	132.65	134.65	2.00	0.02	<0.1	1.77	17	124	<0.5	<5	4.06	1	13	11	36	3.88	1	0.37	<10	0.82	1592	<2	0.02	2	1443	14	0.61	<5	4	149	<5	0.14	<10	<10	49	<10	69	3	
8V3613RA/RJ	HLO8-57	121792	134.65	136.65	2.00	0.05	<0.1	2.00	28	112	<0.5	<5	4.98	1	16	9	48	4.75	<1	0.30	<10	1.03	1951	<2	0.02	2	1526	16	0.90	<5	4	274	<5	0.16	<10	<10	56	<10	87	3	
8V3613RA/RJ	HLO8-57	121793	136.65	138.65	2.00	0.03	0.1	2.01	61	104	<0.5	<5	4.62	2	14	10	45	4.52	<1	0.35	<10	0.98	1890	<2	0.01	2	1343	40	0.79	<5	3	132	<5	0.09	<10	<10	45	<10	155	3	
8V3613RA/RJ	HLO8-57	121794	138.65	140.65	2.00	0.04	<0.1	1.89	33	100	<0.5	<5	4.67	2	13	16	50	4.11	<1	0.30	<10	0.88	1621	2	0.02	2	1484	35	0.59	<5	2	134	<5	0.09	<10	<10	43	<10	145	3	
8V3613RA/RJ	HLO8-57	121795	140.65	142.65	2.00	0.02	0.2	1.71	34	105	<0.5	<5	4.58	2	11	13	42	3.75	<1	0.31	<10	0.79	1463	<2	0.02	2	1324	45	0.56	<5	2	126	<5	0.07	<10	<10	40	<10	142	4	
8V3613RA/RJ	HLO8-57	121796	142.65	144.65	1.51	0.06	<0.1	1.87	48	276	<0.5	<5	4.82	4	11	25	37	3.41	<1	0.29	<10	0.80	1467	2	0.07	3	1347	16	0.62	<5	3	112	<5	0.14	<10	<10	44	<10	283	4	
8V3613RA/RJ	HLO8-57	121797	144.16	145.00	0.84	0.02	<0.1	1.73	<5	594	<0.5	<5	2.21	<1	24	61	15	3.86	1	0.09	19	1.38	617	<2	0.04	13	2259	2	0.17	<5	7	52	<5	0.37	<10	<10	83	<10	106	13	
8V3613RA/RJ	HLO8-57	121798	148.90	149.50	0.60	0.07	<0.1	1.77	<5	39	<0.5	<5	2.17	<1	20	55	21	3.90	1	0.09	19	1.46	695	2	0.04	11	2007														

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0					Ag: 5-10 10-50 50-100 >100					Pb/Zn: 2500-5000 5000-10000 >10000																									
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3634RA/RJ	HL08-58	130503	6.10	7.60	1.50	0.11	1.2	2.43	185	125	<0.5	<5	6.32	4	21	5	34	5.64	<1	0.41	<10	1.01	2257	<2	0.03	2	1616	40	1.50	14	3	160	<5	0.12	<10	<10	59	<10	130	3
8V3634RA/RJ	HL08-58	130504	7.60	9.10	1.50	0.01	0.7	2.61	84	192	<0.5	<5	2.44	2	21	7	33	5.89	<1	0.38	<10	1.32	1956	<2	0.03	3	1762	35	0.74	14	3	64	<5	0.11	<10	<10	73	<10	114	3
8V3634RA/RJ	HL08-58	130505	14.97	16.50	1.53	0.01	<0.1	2.96	17	208	<0.5	<5	2.69	<1	24	31	5	4.93	<1	0.13	12	2.38	1082	<2	0.03	4	1767	27	0.10	14	5	140	<5	0.22	<10	<10	85	<10	128	23
8V3634RA/RJ	HL08-58	130506	16.50	18.00	1.50	0.01	<0.1	3.02	35	116	<0.5	<5	2.42	<1	25	32	12	5.38	<1	0.17	15	2.36	1367	<2	0.04	4	1856	30	0.10	14	6	110	<5	0.19	<10	<10	91	<10	139	19
8V3634RA/RJ	HL08-58	130507	18.00	19.50	1.50	0.01	0.4	3.37	51	189	<0.5	<5	4.11	1	28	8	43	7.19	<1	0.27	<10	1.98	2446	<2	0.07	3	1731	40	0.53	16	6	105	<5	0.18	<10	<10	108	<10	136	5
8V3634RA/RJ	HL08-58	130508	19.50	21.00	1.50	0.01	0.3	2.14	90	125	<0.5	<5	4.32	2	21	8	32	5.56	<1	0.32	<10	1.00	1707	<2	0.03	5	1803	30	1.32	14	4	129	<5	0.15	<10	<10	70	<10	101	4
8V3634RA/RJ	HL08-58	130509	21.00	22.50	1.50	0.02	0.5	2.36	66	127	<0.5	<5	6.84	2	20	5	28	5.38	<1	0.33	<10	1.22	2029	<2	0.03	2	1652	34	1.16	12	4	222	<5	0.11	<10	<10	67	<10	108	4
8V3634RA/RJ	HL08-58	130509A	22.50	24.00	1.50	0.01	0.4	2.36	72	144	<0.5	<5	3.87	2	17	5	28	5.39	<1	0.34	<10	1.23	1730	<2	0.02	2	1637	37	0.91	11	3	145	<5	0.03	<10	<10	62	<10	96	3
8V3634RA/RJ	HL08-58	130510	32.40	33.90	1.50	0.03	0.6	2.32	51	112	<0.5	<5	7.42	4	19	5	26	4.72	<1	0.40	<10	1.11	1798	<2	0.01	2	1456	98	0.60	11	3	153	<5	0.11	<10	<10	47	<10	265	3
8V3634RA/RJ	HL08-58	130511	33.90	35.40	1.50	0.02	0.4	2.45	51	119	<0.5	<5	7.67	2	18	10	21	4.98	<1	0.41	<10	1.11	1967	<2	0.02	2	1647	71	0.60	13	4	165	<5	0.15	<10	<10	50	<10	127	4
8V3634RA/RJ	HL08-58	130512	35.40	36.90	1.50	0.03	0.4	2.08	80	121	<0.5	<5	4.33	2	21	10	38	4.85	<1	0.35	<10	1.04	1671	<2	0.02	3	1815	63	1.11	14	4	129	<5	0.12	<10	<10	63	<10	113	3
8V3634RA/RJ	HL08-58	130513	36.90	38.36	1.46	0.02	0.4	1.99	67	123	<0.5	<5	5.20	2	19	6	27	5.15	<1	0.35	<10	0.94	1586	<2	0.02	2	1679	39	1.41	12	3	158	<5	0.12	<10	<10	55	<10	96	4
8V3634RA/RJ	HL08-58	130514	38.36	39.80	1.44	0.02	0.9	2.50	74	104	<0.5	<5	5.58	2	20	10	30	5.46	<1	0.35	<10	1.27	1997	<2	0.01	2	1733	52	0.88	13	3	147	<5	0.11	<10	<10	58	<10	137	3
8V3634RA/RJ	HL08-58	130515	39.80	41.30	1.50	0.01	0.8	2.55	50	111	<0.5	<5	5.51	2	21	5	33	5.31	<1	0.37	<10	1.30	2197	<2	0.02	2	1829	78	0.57	13	3	149	<5	0.12	<10	<10	63	<10	190	3
8V3634RA/RJ	HL08-58	130516	41.30	42.80	1.50	0.02	0.6	2.27	51	88	<0.5	<5	5.47	1	20	8	26	5.38	<1	0.27	<10	1.26	2005	<2	0.03	2	1752	38	1.46	14	3	138	<5	0.12	<10	<10	67	<10	104	3
8V3634RA/RJ	HL08-58	130517	42.80	44.31	1.51	0.01	0.4	1.70	35	99	<0.5	<5	4.95	<1	14	5	16	4.04	<1	0.29	<10	0.94	1526	<2	0.03	1	1820	24	1.30	11	2	129	<5	0.04	<10	<10	49	<10	44	2
8V3634RA/RJ	HL08-58	130518	46.59	48.10	1.51	0.05	1.6	2.25	711	92	<0.5	<5	6.06	17	19	8	27	5.13	<1	0.36	<10	1.33	2034	<2	0.02	2	1790	68	1.41	16	2	143	<5	0.09	<10	<10	54	<10	164	3
8V3634RA/RJ	HL08-58	130519	48.10	49.59	1.49	0.03	0.9	1.99	105	99	<0.5	<5	6.34	2	18	5	18	5.73	<1	0.30	<10	1.12	1658	<2	0.03	1	1875	28	2.17	16	2	141	<5	0.11	<10	<10	55	<10	61	3
8V3634RA/RJ	HL08-58	130520	49.59	51.10	1.51	0.02	0.5	2.13	54	110	<0.5	<5	6.30	1	22	5	24	6.25	<1	0.29	<10	1.21	1876	<2	0.03	1	1908	33	2.31	17	3	166	<5	0.12	<10	<10	60	<10	74	4
8V3634RA/RJ	HL08-58	130521	51.10	52.60	1.50	0.02	0.3	2.01	57	127	<0.5	<5	4.98	1	19	5	23	5.38	<1	0.35	<10	0.97	1505	<2	0.03	1	1917	33	2.62	16	3	132	<5	0.15	<10	<10	57	<10	75	5
8V3634RA/RJ	HL08-58	130522	52.60	54.10	1.50	0.01	0.4	2.03	54	104	<0.5	<5	6.23	3	17	4	21	5.17	<1	0.32	<10	1.00	1448	<2	0.03	1	1963	65	1.22	13	3	152	<5	0.10	<10	<10	45	<10	191	5
8V3634RA/RJ	HL08-58	130523	54.10	55.60	1.50	0.02	0.4	2.25	64	111	<0.5	<5	3.90	1	20	5	30	5.77	<1	0.33	<10	1.19	1435	<2	0.02	2	1917	45	1.28	15	4	93	<5	0.11	<10	<10	62	<10	88	4
8V3634RA/RJ	HL08-58	130524	55.60	57.15	1.55	0.01	0.2	1.48	66	111	<0.5	<5	3.72	2	35	4	34	4.18	<1	0.33	<10	0.59	1118	<2	0.03	8	2085	40	1.28	13	3	94	<5	0.12	<10	<10	41	<10	72	3
8V3634RA/RJ	HL08-58	130525	Blank	Blank	<0.01	<0.1	0.10	11	16	<0.5	14	>15.00	<1	1	2	1	0.13	<1	0.04	<10	1.99	73	<2	0.01	1	108	<2	0.12	<5	<1	5234	<5	<0.01	<10	25	3	<10	4	<1	
8V3634RA/RJ	HL08-58	130526	57.15	58.70	1.55	0.01	0.2	2.05	33	126	<0.5	<5	4.20	1	23	4	32	5.85	<1	0.34	<10	1.06	1519	<2	0.03	2	2074	38	1.83	15	3	104	<5	0.12	<10	<10	60	<10	141	4
8V3634RA/RJ	HL08-58	130527	58.70	60.20	1.50	0.01	0.3	2.06	45	120	<0.5	<5	4.16	1	20	5	26	6.39	<1	0.34	<10	1.00	1565	<2	0.04	1	1957	53	2.32	14	3	101	<5	0.11	<10	<10	59	<10	108	4
8V3634RA/RJ	HL08-58	130528	60.20	61.70	1.50	0.01	0.3	2.37	32	133	<0.5	<5	6.22	1	17	4	26	5.27	<1	0.31	<10	1.04	1744	<2	0.09	1	1938	44	1.46	12	3	145	<5	0.11	<10	<10	62	<10	164	3
8V3634RA/RJ	HL08-58	130529	67.53	68.95	1.42	0.03	0.6	2.39	49	125	<0.5	<5	4.46	1	17	6	30	4.93	<1	0.40	<10	0.91	1652	<2	0.10	1	2031	39	1.35	11	3	107	<5	0.13	<10	<10	54	<10	100	3
8V3634RA/RJ	HL08-58	130530	68.95	70.50	1.55	0.02	0.8	1.41	51	106	<0.5	<5	3.24	2	17	4	32	4.47	<1	0.37	<10	0.56	1256	<2	0.02	1	2096	40	2.12	12	2	82	<5	0.09	<10	<10	36	<10	190	3
8V3634RA/RJ	HL08-58	130531	70.50	71.70	1.20	0.02	0.8	2.35	65	97	<0.5	<5	5.09	2	21	6	31	6.19	<1	0.36	<10	1.07	2096	<2	0.03	1	1916	50	1.63	15	2	128	<5	0.12	<10	<10	51	<10	199	3
8V																																								

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																										
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3634RA/RJ	HL08-58	130574	208.00	209.50	1.50	0.03	0.5	2.49	61	127	<0.5	<5	4.05	1	20	3	45	6.27	<1	0.32	<10	1.13	1985	<2	0.04	3	1422	11	0.35	<5	3	104	<5	0.03	<10	14	71	<10	125	3
8V3634RA/RJ	HL08-58	130575	Blank	Blank		<0.01	<0.1	0.12	<5	17	<0.5	8	>15.00	<1	1	2	2	0.15	<1	0.04	<10	4.10	96	<2	0.01	1	141	<2	0.05	<5	<1	4285	<5	<0.01	<10	<10	3	<10	5	<1
8V3634RA/RJ	HL08-58	130576	209.50	211.00	1.50	0.03	0.2	1.97	30	121	<0.5	<5	5.01	<1	17	3	30	4.95	<1	0.30	<10	0.94	1871	<2	0.02	3	1585	7	0.29	<5	2	147	<5	0.03	<10	<10	53	<10	85	2
8V3634RA/RJ	HL08-58	130577	211.00	212.50	1.50	0.02	0.6	2.48	39	154	<0.5	<5	4.40	<1	19	3	45	5.90	<1	0.39	<10	1.06	1774	<2	0.02	2	1541	8	0.28	11	2	120	<5	0.04	<10	<10	54	<10	76	3
8V3634RA/RJ	HL08-58	130578	212.50	214.00	1.50	0.02	1.3	4.08	59	253	<0.5	7	7.89	1	40	6	74	9.24	<1	0.69	14	1.80	3137	<2	0.05	6	3030	35	0.87	17	5	214	<5	0.07	<10	<10	104	<10	299	4
8V3634RA/RJ	HL08-58	130579	221.12	221.68	0.56	0.02	0.6	2.19	22	105	2.6	5	5.73	<1	22	6	35	5.30	<1	0.42	<10	1.13	2130	<2	0.02	3	1609	24	0.61	10	4	129	<5	0.01	<10	<10	57	<10	127	2
8V3634RA/RJ	HL08-58	130580	223.65	224.42	0.77	0.01	0.1	2.46	27	145	<0.5	<5	6.07	<1	67	6	13	4.42	<1	0.44	<10	1.11	2126	<2	0.09	1	1497	26	0.26	9	4	110	<5	0.08	<10	<10	57	<10	106	2
8V3634RA/RJ	HL08-58	130581	224.87	226.40	1.53	0.02	0.6	2.25	63	112	<0.5	<5	6.30	1	17	5	23	5.48	<1	0.33	<10	1.04	1905	<2	0.02	2	1605	40	0.60	10	2	135	<5	0.05	<10	<10	48	<10	106	2
8V3634RA/RJ	HL08-58	130582	226.40	227.90	1.50	0.02	1.1	2.05	96	100	<0.5	<5	6.93	3	15	9	34	4.81	<1	0.31	<10	1.02	2049	<2	0.01	2	1388	73	0.46	9	2	287	<5	0.03	<10	<10	40	<10	206	2
8V3634RA/RJ	HL08-58	130583	227.90	229.40	1.50	0.02	0.9	2.17	40	120	<0.5	<5	5.23	<1	19	5	48	5.40	<1	0.34	10	1.04	1598	<2	0.02	2	1670	11	0.62	10	2	121	<5	0.05	<10	<10	49	<10	80	2
8V3634RA/RJ	HL08-58	130584	229.40	230.68	1.28	0.09	1.2	2.03	102	123	<0.5	<5	2.56	2	22	6	52	5.40	<1	0.34	<10	1.03	1275	<2	0.01	3	1637	18	1.04	11	2	76	<5	0.03	<10	<10	42	<10	86	2
8V3634RA/RJ	HL08-58	130585	230.68	232.09	1.41	0.02	1.0	2.35	95	120	<0.5	<5	3.57	2	21	3	36	5.49	<1	0.36	<10	1.26	1576	<2	0.01	2	1651	15	0.45	11	2	99	<5	0.04	<10	<10	48	<10	149	2
8V3634RA/RJ	HL08-58	130586	232.09	233.30	1.21	0.08	1.8	2.15	441	109	<0.5	<5	4.67	10	18	20	51	5.71	<1	0.30	<10	1.38	1566	<2	0.01	5	1858	24	1.37	15	4	143	<5	0.06	<10	<10	45	<10	109	3
8V3634RA/RJ	HL08-58	130587	233.30	234.50	1.20	0.01	1.1	2.61	62	120	<0.5	<5	4.42	1	21	26	53	5.91	<1	0.30	<10	1.98	1491	<2	0.01	7	2138	8	0.68	14	5	153	<5	0.09	<10	<10	67	<10	96	3
8V3634RA/RJ	HL08-58	130588	234.50	235.70	1.20	0.02	0.9	2.18	182	121	<0.5	<5	4.83	4	18	21	56	5.24	<1	0.33	<10	1.48	1291	<2	0.01	5	2254	10	1.17	13	4	142	<5	0.04	<10	<10	47	<10	95	3
8V3634RA/RJ	HL08-58	130589	235.70	237.20	1.50	0.01	0.5	2.47	45	115	<0.5	<5	4.28	1	17	24	44	5.36	<1	0.25	<10	1.71	1514	<2	0.01	6	1950	14	0.19	11	5	131	<5	0.06	<10	<10	61	<10	106	3
8V3634RA/RJ	HL08-58	130590	237.20	238.64	1.44	<0.01	0.3	2.70	45	144	<0.5	<5	3.61	1	15	23	41	5.64	<1	0.27	<10	1.88	1438	<2	0.01	5	2037	10	0.06	10	5	129	<5	0.02	<10	<10	61	<10	96	3
8V3634RA/RJ	HL08-58	130591	238.64	239.94	1.30	0.01	0.5	2.67	42	127	0.8	5	4.72	1	19	30	43	5.79	<1	0.30	12	1.82	1467	<2	0.02	8	2159	48	0.49	9	5	259	<5	0.01	<10	<10	61	<10	152	3
8V3634RA/RJ	HL08-58	130592	239.94	241.08	1.14	0.03	0.9	1.97	73	77	0.6	6	11.44	2	16	33	33	4.63	<1	0.20	10	1.49	3163	<2	0.02	6	1520	220	0.97	8	8	350	<5	<0.01	<10	<10	87	<10	142	2
8V3634RA/RJ	HL08-58	130593	241.08	242.60	1.52	0.07	1.0	2.93	88	76	0.7	5	7.13	4	27	56	84	6.89	<1	0.19	<10	2.58	2190	<2	0.01	12	1768	69	1.59	13	11	229	<5	0.01	<10	<10	154	<10	387	3
8V3634RA/RJ	HL08-58	130594	242.60	244.10	1.50	0.04	0.7	2.87	71	80	0.7	5	5.01	1	30	53	84	6.94	<1	0.19	<10	2.78	1694	<2	0.02	12	2051	42	1.92	13	11	156	<5	0.01	<10	<10	172	<10	123	3
8V3634RA/RJ	HL08-58	130595	244.10	245.16	1.06	0.03	0.9	2.88	58	66	0.7	5	4.98	1	27	51	83	6.75	<1	0.14	<10	2.73	1703	<2	0.01	11	1904	63	1.29	12	12	162	<5	0.01	<10	<10	175	<10	139	3
8V3634RA/RJ	HL08-58	130596	245.16	246.43	1.27	0.10	0.9	2.68	84	68	0.7	5	6.51	5	28	47	102	6.81	<1	0.13	<10	2.37	1839	<2	0.02	11	1806	279	1.85	12	11	205	<5	0.01	<10	<10	165	11	582	3
8V3634RA/RJ	HL08-58	130597	250.15	251.65	1.50	0.05	0.4	2.96	85	75	0.9	5	6.33	2	28	66	77	6.41	<1	0.14	<10	2.88	2238	<2	0.01	14	1847	45	1.29	12	14	228	<5	0.01	<10	<10	186	<10	154	3
8V3634RA/RJ	HL08-58	130598	251.65	253.10	1.45	0.05	0.7	2.90	149	80	0.9	6	8.04	3	28	68	61	6.65	<1	0.20	<10	2.57	2435	<2	0.01	14	1819	33	1.64	13	13	275	<5	0.01	<10	<10	158	<10	115	3
8V3634RA/RJ	HL08-58	130599	253.10	254.60	1.50	0.03	0.6	2.76	97	90	<0.5	6	10.19	2	30	66	35	6.51	<1	0.20	<10	2.15	3345	<2	0.01	16	1860	12	1.47	<5	13	274	<5	<0.01	<10	18	160	80	3	
8V3634RA/RJ	HL08-58	130600	Std	PM11.6		0.12	810.0	0.57	607	187	<0.5	115	0.55	23	7	19	7290	2.25	7	0.15	<10	0.55	287	585	0.02	5	419	924	1.18	1762	1	73	<5	0.05	<10	<10	18	<10	994	2
8V3634RA/RJ	HL08-58	130601	254.60	255.60	1.00	0.03	0.9	3.26	127	82	<0.5	6	5.90	2	28	80	50	6.90	<1	0.13	<10	2.94	2563	<2	0.01	15	1807	31	0.96	<5	14	161	<5	0.01	<10	<10	149	<10	101	3
8V3634RA/RJ	HL08-58	130602	255.60	256.80	1.20	0.12	3.3	2.47	610	73	<0.5	6	6.67	21	29	35	123	6.60	<1	0.21	<10	2.04	2337	<2	0.01	15	1643	964	2.70	<5	7	177	<5	0.01	<10	17	90	16	911	3
8V3634RA/RJ	HL08-58	130603	256.80	258.00	1.20	0.02	0.7	3.50	110	83	<0.5	<5	5.17	4	30	53	105	6.72	<1	0.18	<10	3.19	2047	<2	0.01	14	1812	41	0.40	<5	10	177	<5	0.03	<10	13	145	<10	303	3
8V3634RA/RJ	HL08-58	130604	258.00	259.00	1.00	0.04	0.5	2.99	104	146	<0.5	<5	5.87	2	28	44	92	6.05	<1	0.31	<10	2.47	1872	<2	0.01	13	1707	28	0.78	<5	10	209	<5	0.03	<10	<10	122	<10	130	3
8V3634RA/RJ	HL08-58	130605	259.00	259.93	0.93	0.04	0.5	2.90	94	215	<0.5	<5	5.22	2	31	51	94	6.30	<1	0.50	<10	2.26	1871	<2	0.02	14	2025	20	1.26	<5	12	205	<5	0.03	<10	12	142	<10	111	3
8V3634RA/RJ	HL08-58	130606	274.53	275.47	0.94	0.03	1.8	2.52	117	89	<0.5	<5	4.38	8	37	47	126	6.59	<1	0.17	<10	2.39	1944	<2	0.03	15	1924	564	2.60	<5	16	191	<5	0.13	<10	10	227	18	1007	5
8V3634RA/RJ	HL08-58	130607	275.47	276.27	0.80	0.06	1.1	2.20	88	88	<0.5	<5	4.10	2	33	42	93	6.29	<1																					

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																											
					0.1-0.3	0.3-0.5	>0.5	10-50	50-100	>100	2500-5000	5000-10000	>10000	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Zr															
8V3634RA/RJ	HL08-58	130646	357.60	359.10	1.50	0.01	0.8	3.42	71	31	<0.5	<5	8.67	1	37	286	90	6.32	<1	0.03	<10	4.00	2352	<2	0.01	43	1844	12	1.67	<5	28	285	<5	0.11	<10	11	234	<10	97	4
8V3634RA/RJ	HL08-58	130647	359.10	359.64	0.54	0.01	1.7	3.00	93	51	<0.5	<5	9.63	2	39	263	91	6.25	<1	0.07	<10	3.22	2352	<2	0.02	45	1879	16	2.25	<5	21	288	<5	0.10	<10	13	183	<10	76	4
8V3634RA/RJ	HL08-58	130648	366.62	368.10	1.48	0.05	2.8	2.95	126	208	<0.5	<5	5.53	5	33	94	93	6.54	<1	0.42	<10	2.20	1700	<2	0.06	20	2139	39	2.57	<5	13	146	<5	0.10	<10	13	128	<10	407	4
8V3634RA/RJ	HL08-58	130649	368.10	369.60	1.50	0.03	1.5	3.09	82	119	<0.5	<5	5.82	2	30	45	78	7.06	<1	0.24	<10	2.24	1897	<2	0.03	14	2258	42	1.26	<5	8	154	<5	0.04	<10	14	104	<10	149	4
8V3634RA/RJ	HL08-58	130650	Std	PM1116		0.12	806.5	6.00	616	196	<0.5	<112	0.58	23	8	19	7449	2.36	7	0.15	<10	0.58	294	589	0.03	5	422	941	1.19	1819	2	75	<5	0.06	<10	19	<10	1009	2	
8V3634RA/RJ	HL08-58	130651	369.60	371.04	1.44	0.01	2.7	2.57	139	106	<0.5	<5	5.97	4	26	27	78	6.51	<1	0.21	<10	1.94	1821	<2	0.01	12	2034	60	1.86	<5	6	161	<5	0.02	<10	12	74	<10	191	3
8V3634RA/RJ	HL08-58	130652	371.04	372.54	1.50	0.05	1.3	2.34	80	107	<0.5	<5	6.10	2	24	23	63	5.76	<1	0.19	<10	1.63	1723	<2	0.01	10	1965	13	1.38	<5	6	167	<5	0.01	<10	10	60	<10	89	3
8V3634RA/RJ	HL08-58	130653	372.54	374.00	1.46	0.01	1.9	2.13	116	94	<0.5	<5	7.20	2	25	22	71	5.94	<1	0.21	<10	1.42	2166	<2	0.01	11	2102	20	2.17	<5	6	177	<5	0.02	<10	12	52	<10	83	3
8V3634RA/RJ	HL08-58	130654	374.00	375.25	1.25	0.06	2.5	2.09	174	87	<0.5	<5	7.82	4	28	24	77	6.29	<1	0.20	<10	1.48	2257	<2	0.01	12	2131	27	2.87	<5	6	174	<5	0.01	<10	13	55	<10	131	3
8V3634RA/RJ	HL08-58	130655	375.25	376.27	1.02	0.05	1.9	2.38	130	104	<0.5	<6	6.60	3	28	26	68	6.60	<1	0.25	<10	1.68	1928	<2	0.01	12	2033	33	2.47	<5	7	194	<5	0.01	<10	16	64	<10	122	3
8V3634RA/RJ	HL08-58	130656	376.70	378.20	1.50	0.04	1.4	2.53	150	86	<0.5	<5	7.37	3	25	34	72	6.07	<1	0.21	<10	1.80	2032	<2	0.01	11	2113	13	1.32	<5	6	210	<5	0.01	<10	16	66	<10	107	3
8V3634RA/RJ	HL08-58	130657	378.20	379.70	1.50	0.03	0.6	2.28	60	93	<0.5	<5	5.98	2	19	19	45	5.38	<1	0.23	<10	1.29	2232	<2	0.01	7	1915	35	0.65	<5	5	145	<5	0.01	<10	12	43	<10	128	2
8V3634RA/RJ	HL08-58	130658	379.70	381.20	1.50	0.04	0.9	2.51	141	95	<0.5	<6	7.08	3	21	35	55	5.45	<1	0.23	<10	1.56	2547	<2	0.01	9	1985	18	0.45	<5	6	151	<5	0.01	<10	11	67	<10	114	2
8V3634RA/RJ	HL08-58	130659	381.20	382.70	1.50	0.03	1.2	2.86	68	86	<0.5	<6	6.62	1	27	33	78	6.53	<1	0.20	<10	1.64	2364	<2	0.01	13	2073	9	0.43	<5	7	144	<5	0.01	<10	12	77	<10	114	3
8V3634RA/RJ	HL08-58	130660	382.70	384.20	1.50	0.03	0.8	2.40	89	116	<0.5	<5	6.50	2	24	31	59	5.41	<1	0.29	<10	1.19	2183	<2	0.01	10	2056	9	0.24	<5	7	137	<5	0.02	<10	10	62	<10	108	2
8V3634RA/RJ	HL08-58	130661	384.20	385.28	1.08	0.04	0.9	2.50	27	153	<0.5	<5	4.68	<1	20	33	77	5.02	<1	0.56	<10	0.96	1780	3	0.06	7	1933	15	0.55	<5	9	69	<5	0.08	<10	10	77	<10	111	4
8V3634RA/RJ	HL08-58	130662	389.49	391.05	1.56	0.02	1.0	2.37	58	152	<0.5	<5	4.66	2	26	11	74	5.62	<1	0.45	<10	0.90	1898	<2	0.03	7	1625	62	0.61	<5	5	90	<5	0.04	<10	10	59	<10	168	3
8V3634RA/RJ	HL08-58	130663	393.65	395.10	1.45	0.18	1.6	2.11	86	139	<0.5	<5	6.16	2	22	6	114	5.23	<1	0.36	<10	0.76	1918	<2	0.03	4	1536	60	1.08	<5	3	118	<5	0.03	<10	10	47	<10	119	2
8V3634RA/RJ	HL08-58	130664	395.10	396.60	1.50	0.01	0.9	2.17	34	116	<0.5	<5	4.70	1	19	4	66	5.45	<1	0.26	<10	0.85	1866	<2	0.01	3	1573	14	0.34	<5	3	89	<5	<0.01	<10	10	44	<10	99	2
8V3634RA/RJ	HL08-58	130665	396.60	398.10	1.50	0.04	0.7	2.68	79	144	<0.5	<5	6.14	1	18	3	38	6.32	<1	0.34	<10	0.94	2053	<2	0.02	2	1518	16	0.35	11	3	110	<5	0.01	<10	10	50	<10	109	3
8V3634RA/RJ	HL08-58	130666	398.10	399.60	1.50	0.01	0.6	2.84	26	142	<0.5	<5	5.53	<1	20	5	35	6.97	<1	0.34	<10	1.07	2071	<2	0.02	1	1709	21	0.28	12	3	100	<5	0.02	<10	10	52	<10	128	3
8V3634RA/RJ	HL08-58	130667	399.60	401.10	1.50	0.03	0.7	1.90	28	132	<0.5	<5	5.77	<1	15	17	29	4.73	<1	0.34	<10	0.62	1539	<2	0.02	2	1516	16	0.39	8	2	102	<5	0.02	<10	10	28	<10	88	2
8V3634RA/RJ	HL08-58	130668	401.10	402.60	1.50	0.02	0.9	2.42	53	138	<0.5	<5	5.60	1	21	5	32	9.22	<1	0.36	<10	0.85	1931	3	0.04	2	1648	24	0.69	12	3	95	<5	0.05	<10	10	42	<10	97	2
8V3634RA/RJ	HL08-58	130669	402.60	404.12	1.52	0.07	0.9	4.18	116	267	<0.5	<5	6.89	2	20	11	36	5.39	<1	1.05	<10	1.01	2140	<2	0.20	3	1616	16	0.28	13	5	117	<5	0.12	<10	10	81	<10	94	3
8V3634RA/RJ	HL08-58	130670	425.31	426.74	1.43	0.01	0.5	4.82	24	112	<0.5	<5	4.17	<1	17	30	76	4.55	<1	0.33	<10	1.00	846	<2	0.41	3	1600	9	0.31	13	5	124	<5	0.19	<10	10	95	<10	122	5
8V3634RA/RJ	HL08-58	130671	450.89	452.40	1.51	<0.01	<0.1	6.21	30	247	<0.5	<5	5.59	<1	20	16	26	5.50	<1	0.95	<10	1.28	1448	<2	0.40	2	1596	8	0.19	15	6	130	<5	0.21	<10	10	37	<10	116	5
8V3634RA/RJ	HL08-58	130672	452.40	453.90	1.50	0.01	0.2	5.00	29	275	<0.5	<5	5.96	<1	18	12	27	4.60	<1	0.87	<10	1.05	1280	<2	0.32	2	1518	8	0.32	12	5	135	<5	0.15	<10	10	75	<10	102	3
8V3634RA/RJ	HL08-58	130673	453.90	455.40	1.50	0.01	0.2	4.34	36	297	<0.5	<5	6.00	<1	20	6	31	5.48	<1	0.85	<10	1.18	1571	<2	0.20	2	1530	4	0.29	13	5	123	<5	0.12	<10	10	67	<10	102	3
8V3634RA/RJ	HL08-58	130674	455.40	456.90	1.50	0.01	0.3	3.10	22	159	<0.5	<5	5.32	<1	18	7	28	5.02	<1	0.46	<10	1.02	1466	<2	0.13	2	1523	9	0.34	12	3	104	<5	0.08	<10	10	42	<10	93	2
8V3634RA/RJ	HL08-58	130675	Blank	Blank		0.01	<0.1	0.29	9	17	<0.5	<11	>15.00	<1	2	13	2	0.37	<1	0.05	<10	5.08	162	<2	0.01	5	189	<2	0.08	<5	1	2979	<5	<0.01	<10	17	8	<10	5	<1
8V3634RA/RJ	HL08-58	130676	456.90	458.40	1.50	0.01	0.5	2.32	25	1																														

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																											
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm	
						0.5-1.0	1.0-3.0	3.0-5.0	>5.0	5-10	10-50	50-100	>100	2500-5000		5000-10000		>10000																							
8V3633RA/RJ	HL08-59	121866	27.22	28.32	1.10	0.74	6.7	1.75	96	129	<0.5	<5	4.66	56	16	7	466	5.16	<1	0.23	<10	0.93	2350	112	0.01	2	1327	1194	1.36	<5	3	122	<5	0.01	<10	<10	11	66	110	6721	2
8V3633RA/RJ	HL08-59	121867	28.32	29.57	1.25	1.38	5.9	2.24	88	62	<0.5	<5	6.99	5	25	5	601	5.99	<1	0.16	<10	1.43	3123	117	0.01	5	1305	19	0.57	<5	6	238	<5	0.01	<10	15	91	<10	432	2	
8V3633RA/RJ	HL08-59	121868	29.57	31.07	1.50	1.74	5.5	2.00	82	71	<0.5	<5	8.13	6	17	9	706	5.87	<1	0.23	<10	1.16	2872	64	0.02	<1	1035	58	1.21	11	5	132	<5	0.02	<10	<10	211	<10	626	4	
8V3633RA/RJ	HL08-59	121869	31.07	32.50	1.43	1.97	7.1	1.56	127	65	<0.5	<5	8.17	11	14	30	952	5.30	<1	0.17	<10	0.93	2615	74	0.03	<1	963	104	1.13	10	6	132	<5	0.01	<10	<10	189	11	803	4	
8V3633RA/RJ	HL08-59	121870	32.50	34.00	1.50	0.98	3.1	1.79	40	81	<0.5	<5	4.11	17	15	12	766	5.06	<1	0.26	<10	1.01	1894	59	0.03	<1	1306	422	0.75	11	5	75	<5	0.05	<10	<10	203	21	1491	4	
8V3633RA/RJ	HL08-59	121871	34.00	35.50	1.50	0.80	<0.1	2.00	138	58	<0.5	<5	8.53	11	17	<1	695	5.95	<1	0.18	<10	1.20	2798	28	0.04	<1	1045	57	1.32	11	6	135	<5	0.05	<10	<10	224	12	777	4	
8V3633RA/RJ	HL08-59	121872	35.50	36.50	1.00	0.61	<0.1	1.99	130	90	<0.5	<5	6.84	9	15	114	463	5.38	<1	0.22	<10	1.40	2774	28	0.04	<1	1085	64	1.20	11	7	120	<5	0.03	<10	<10	204	14	1000	4	
8V3633RA/RJ	HL08-59	121873	36.50	37.50	1.00	1.23	0.7	2.07	178	54	<0.5	<5	5.18	19	15	7	933	6.77	<1	0.12	<10	1.24	2763	7	0.03	<1	1121	117	1.58	13	7	97	<5	0.05	<10	<10	276	16	1167	5	
8V3633RA/RJ	HL08-59	121874	37.50	38.72	1.22	1.49	7.1	2.07	212	65	<0.5	<5	5.21	29	21	11	1236	7.38	<1	0.15	<10	1.25	2659	26	0.04	<1	1148	104	2.28	14	6	102	<5	0.02	<10	<10	271	26	1991	5	
8V3633RA/RJ	HL08-59	121875	Blank	Blank	Blank	0.01	4.1	0.06	11	12	<0.5	13	>15.00	<1	1	11	11	0.13	<1	0.01	<10	2.21	110	2	<0.01	1	82	<2	0.09	<5	<1	5936	<5	<0.01	<10	<10	6	<10	16	<1	
8V3633RA/RJ	HL08-59	121876	38.72	40.22	1.50	0.07	<0.1	2.28	52	121	<0.5	<5	7.11	3	15	<1	162	6.02	<1	0.30	<10	1.61	2906	13	0.02	<1	1102	128	0.78	11	4	116	<5	<0.01	<10	<10	193	<10	481	4	
8V3633RA/RJ	HL08-59	121877	40.22	41.70	1.48	0.05	<0.1	2.30	26	107	<0.5	<5	4.48	23	16	<1	246	5.93	<1	0.30	<10	1.66	2406	12	0.02	<1	1164	694	0.98	12	4	91	<5	0.02	<10	<10	201	39	2992	4	
8V3633RA/RJ	HL08-59	121878	41.70	43.20	1.50	0.14	<0.1	2.02	81	104	<0.5	<5	6.63	6	17	67	265	5.30	<1	0.29	<10	1.45	2565	24	0.03	<1	1174	158	1.14	11	6	110	<5	0.02	<10	<10	200	10	709	4	
8V3633RA/RJ	HL08-59	121879	43.20	44.70	1.50	0.23	<0.1	1.58	125	100	<0.5	<5	5.68	12	21	196	299	4.79	<1	0.20	<10	1.21	2034	49	0.01	<1	1394	282	1.69	12	9	87	<5	0.01	<10	<10	225	18	1277	3	
8V3633RA/RJ	HL08-59	121880	44.70	46.20	1.50	0.27	1.9	1.22	216	57	<0.5	<5	8.83	14	17	398	295	4.20	<1	0.13	<10	1.02	2868	37	0.02	13	968	88	1.85	12	9	136	<5	0.01	<10	<10	198	19	1406	4	
8V3633RA/RJ	HL08-59	121881	46.20	47.70	1.50	0.15	0.5	1.72	241	75	<0.5	<5	9.98	10	29	688	401	5.63	<1	0.15	<10	1.38	3323	38	<0.01	35	1612	63	1.61	16	18	188	<5	0.02	<10	<10	303	<10	535	4	
8V3633RA/RJ	HL08-59	121882	47.70	49.13	1.43	0.03	<0.1	1.96	144	61	<0.5	<5	14.90	8	32	880	187	5.20	<1	0.08	<10	1.67	3722	75	<0.01	34	1534	35	0.65	15	23	241	<5	0.05	<10	<10	359	11	536	6	
8V3633RA/RJ	HL08-59	121883	49.13	50.53	1.40	0.05	0.3	1.80	152	49	<0.5	<5	13.58	9	34	856	318	4.66	<1	0.07	<10	1.63	3057	57	<0.01	42	1529	39	0.84	16	20	183	<5	0.08	<10	<10	343	<10	551	5	
8V3633RA/RJ	HL08-59	121884	50.53	52.53	2.00	0.04	2.9	1.30	95	41	<0.5	<5	>15.00	8	22	546	283	3.68	<1	0.05	<10	1.11	4224	12	0.01	22	1100	21	0.65	12	287	<5	0.06	<10	<10	269	<10	514	4		
8V3633RA/RJ	HL08-59	121885	52.53	54.20	1.67	0.03	<0.1	2.08	108	28	<0.5	<5	>15.00	4	28	784	192	5.05	<1	0.07	<10	1.88	3572	105	0.01	33	1336	33	0.52	13	21	197	<5	0.03	<10	<10	317	<10	256	4	
8V3633RA/RJ	HL08-59	121886	54.20	56.20	2.00	0.04	<0.1	2.19	75	35	<0.5	<5	10.37	8	32	814	262	5.48	<1	0.06	<10	2.07	2706	30	<0.01	34	1563	34	0.67	17	16	192	<5	0.10	<10	<10	326	<10	523	6	
8V3633RA/RJ	HL08-59	121887	56.20	58.20	2.00	0.03	<0.1	2.23	59	43	<0.5	<5	7.00	7	29	1091	161	5.26	<1	0.06	<10	2.44	2092	5	<0.01	38	1814	39	0.35	18	14	127	<5	0.12	<10	<10	370	<10	486	6	
8V3633RA/RJ	HL08-59	121888	58.20	59.62	1.42	0.01	<0.1	2.23	43	52	<0.5	<5	8.98	3	27	996	85	4.92	<1	0.08	<10	2.50	1771	2	0.01	37	1862	31	0.14	15	14	177	<5	0.12	<10	<10	337	<10	259	5	
8V3633RA/RJ	HL08-59	121889	59.62	60.59	0.97	0.02	<0.1	2.09	55	43	<0.5	<5	9.00	12	30	975	39	4.75	<1	0.06	<10	2.38	1963	2	<0.01	46	1761	29	0.27	15	15	156	<5	0.12	<10	<10	353	10	597	5	
8V3633RA/RJ	HL08-59	121890	60.59	62.13	1.54	0.06	<0.1	2.53	103	26	<0.5	<5	10.87	19	35	898	296	6.06	<1	0.06	<10	2.48	2769	15	0.01	39	1500	59	0.91	17	23	182	<5	0.06	<10	<10	400	16	1073	5	
8V3633RA/RJ	HL08-59	121891	62.13	63.60	1.47	0.59	0.5	1.94	110	39	<0.5	<5	8.89	10	21	423	478	5.73	<1	0.12	<10	1.53	2510	24	0.03	16	1206	63	1.42	14	15	111	<5	0.07	<10	<10	280	11	780	5	
8V3633RA/RJ	HL08-59	121892	63.60	65.10	1.50	0.15	<0.1	2.16	127	33	<0.5	<5	12.11	27	27	681	232	5.83	<1	0.06	<10	2.08	3094	8	<0.01	26	1360	705	1.46	16	18	208	<5	0.07	<10	<10	341	32	2372	6	
8V3633RA/RJ	HL08-59	121893	65.10	66.60	1.50	0.02	<0.1	2.74	54	38	<0.5	<5	10.44	11	25	631	78	5.61	<1	0.11	<10	2.44	2511	2	0.01	25	1698	48	0.51	15	20	178	<5	0.08	<10	<10	397	12	773	6	
8V3633RA/RJ	HL08-59	121894	66.60	68.10	1.50	0.01	<0.1	2.28	34	38	<0.5	<5	9.54	9	19	213	39	5.22	<1	0.24	<10	1.79	1821	<2	0.02	10	1473	98	0.47	12	11	151	<5	0.11	<10	<10	234	11	676	4	
8V3633RA/RJ	HL08-59	121895	68.10	69.60	1.50	0.01	<0.1	2.91	20	42	<																														

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3633RA/RJ	HL08-59	121937	136.70	138.55	1.85	0.01	0.4	2.23	9	68	<0.5	<5	3.32	<1	16	4	48	5.04	<1	0.21	<10	1.39	1875	<2	0.03	2	1285	133	0.42	10	4	109	<5	0.05	<10	<10	82	<10	198	3
8V3633RA/RJ	HL08-59	121938	138.55	140.41	1.86	<0.01	<0.1	2.33	15	69	<0.5	<5	5.02	<1	17	5	22	4.55	<1	0.22	<10	1.46	1682	<2	0.03	1	1291	25	0.29	10	4	176	<5	0.09	<10	<10	73	<10	81	4
8V3633RA/RJ	HL08-59	121939	140.41	142.20	1.79	<0.01	<0.1	2.76	20	152	<0.5	<5	2.67	<1	19	8	38	4.83	<1	0.57	<10	1.21	1384	<2	0.14	2	1377	32	0.54	11	5	107	<5	0.14	<10	<10	96	<10	89	4
8V3633RA/RJ	HL08-59	121940	153.77	154.83	1.06	0.02	0.3	2.15	23	128	<0.5	<5	3.97	1	14	11	43	4.16	<1	0.47	<10	1.15	1268	<2	0.06	2	1189	88	0.82	8	5	106	<5	0.05	<10	<10	86	<10	162	3
8V3633RA/RJ	HL08-59	121941	154.83	156.58	1.75	0.02	0.3	2.82	32	127	<0.5	<5	2.91	1	18	33	42	4.88	<1	0.81	<10	1.14	1466	<2	0.10	3	1239	115	0.93	11	5	103	<5	0.12	<10	<10	85	<10	168	3
8V3633RA/RJ	HL08-59	121942	156.58	158.50	1.92	0.02	<0.1	2.34	13	76	<0.5	<5	4.11	<1	20	5	18	5.38	<1	0.30	<10	1.41	1953	<2	0.03	2	1309	43	0.51	11	5	127	<5	0.13	<10	<10	81	<10	93	3
8V3633RA/RJ	HL08-59	121943	158.50	160.50	2.00	0.03	<0.1	2.27	15	68	<0.5	<5	4.65	<1	20	5	32	5.48	<1	0.24	<10	1.31	1893	<2	0.02	2	1368	27	0.43	11	5	156	<5	0.12	<10	<10	79	<10	91	3
8V3633RA/RJ	HL08-59	121944	160.50	162.50	2.00	0.04	0.2	2.11	16	80	<0.5	<5	4.66	<1	17	4	27	4.94	<1	0.27	<10	1.18	1936	<2	0.02	2	1296	63	0.45	10	4	127	<5	0.12	<10	<10	68	<10	136	3
8V3633RA/RJ	HL08-59	121945	162.50	164.50	2.00	0.01	<0.1	1.86	9	84	<0.5	<5	4.91	<1	18	6	30	4.52	<1	0.25	<10	0.99	1627	<2	0.03	2	1298	26	0.46	9	4	159	<5	0.13	<10	<10	67	<10	76	3
8V3633RA/RJ	HL08-59	121946	164.50	166.00	1.50	0.01	0.3	2.03	14	81	<0.5	<5	3.29	1	17	15	29	4.98	<1	0.21	<10	1.21	1964	<2	0.02	3	1298	77	0.53	10	4	92	<5	0.11	<10	<10	76	<10	333	3
8V3633RA/RJ	HL08-59	121947	166.00	167.41	1.41	0.01	0.4	1.82	19	126	<0.5	<5	3.46	2	17	4	23	5.15	<1	0.28	<10	0.88	1896	<2	0.02	2	1351	175	1.24	10	4	105	<5	0.12	<10	<10	68	<10	352	3
8V3633RA/RJ	HL08-59	121948	167.41	169.09	1.68	0.01	0.1	1.82	14	141	<0.5	<5	4.05	1	15	5	18	4.45	<1	0.34	<10	0.78	1804	<2	0.02	1	1336	67	0.64	9	3	127	<5	0.12	<10	<10	60	<10	166	3
8V3633RA/RJ	HL08-59	121949	169.09	170.59	1.50	0.01	0.5	2.06	29	104	<0.5	<5	5.17	4	17	4	30	4.94	<1	0.26	<10	1.14	2352	<2	0.02	1	1243	211	0.66	10	3	122	<5	0.08	<10	<10	64	<10	565	2
8V3633RA/RJ	HL08-59	121950	Std	PM1116		0.18	801.0	0.57	545	172	<0.5	65	0.52	19	7	18	7594	2.11	5	0.15	<10	0.55	268	548	0.03	4	238	889	1.07	1640	2	73	<5	0.05	<10	<10	18	<10	957	2
8V3633RA/RJ	HL08-59	121951	170.59	172.00	1.41	0.02	2.1	1.81	26	115	<0.5	<5	5.65	1	17	4	29	4.52	<1	0.32	<10	0.90	2488	<2	0.02	1	1347	59	0.78	13	3	106	<5	0.10	<10	<10	57	<10	161	2
8V3633RA/RJ	HL08-59	121952	172.00	173.60	1.60	0.05	2.3	1.71	79	74	<0.5	<5	11.48	2	13	9	16	4.93	<1	0.23	<10	1.01	4172	<2	0.01	1	882	122	1.49	12	3	203	<5	0.07	<10	<10	47	<10	248	2
8V3633RA/RJ	HL08-59	121953	173.60	175.60	2.00	0.02	0.6	2.03	21	89	<0.5	<5	4.51	<1	16	5	31	4.73	<1	0.34	<10	1.12	1808	<2	0.02	1	1332	58	0.61	10	3	122	<5	0.10	<10	<10	51	<10	107	3
8V3633RA/RJ	HL08-59	121954	175.60	177.60	2.00	0.02	0.4	2.01	40	93	<0.5	<5	4.46	1	17	6	10	5.04	<1	0.33	<10	1.03	2097	<2	0.02	1	1365	63	0.75	10	3	133	<5	0.10	<10	<10	51	<10	144	2
8V3633RA/RJ	HL08-59	121955	177.60	179.60	2.00	0.02	0.1	1.92	13	131	<0.5	<5	4.60	1	19	25	31	5.05	<1	0.42	<10	0.86	1927	<2	0.02	3	1623	60	0.70	10	5	136	<5	0.11	<10	<10	59	<10	115	3
8V3633RA/RJ	HL08-59	121956	179.60	181.60	2.00	0.01	<0.1	2.04	6	105	<0.5	<5	3.89	1	18	14	24	5.33	<1	0.30	<10	1.13	1977	<2	0.02	3	1555	70	0.58	5	4	109	<5	0.09	<10	<10	62	<10	122	3
8V3633RA/RJ	HL08-59	121957	181.60	183.60	2.00	0.02	<0.1	2.08	5	107	<0.5	<5	5.21	<1	18	19	13	4.99	<1	0.31	<10	1.18	1932	<2	0.02	4	1563	25	0.39	5	4	155	<5	0.12	<10	<10	60	<10	92	3
8V3633RA/RJ	HL08-59	121958	183.60	185.60	2.00	0.01	<0.1	1.85	8	146	<0.5	<5	5.49	<1	17	14	26	4.48	<1	0.38	<10	0.96	1834	<2	0.02	3	1463	37	0.49	5	4	169	<5	0.12	<10	<10	49	<10	85	3
8V3633RA/RJ	HL08-59	121959	185.60	186.44	0.84	0.02	0.1	1.13	8	120	<0.5	<5	4.69	<1	20	6	26	5.48	<1	0.34	<10	1.16	1975	<2	0.02	3	1577	73	0.75	5	3	128	<5	0.11	<10	<10	55	<10	105	3
8V3633RA/RJ	HL08-59	121960	186.44	187.41	0.97	0.44	7.9	1.79	113	107	<0.5	<5	9.24	75	16	24	445	5.55	<1	0.27	<10	1.00	3204	<2	0.01	3	1168	3182	2.52	5	2	469	<5	0.06	<10	22	36	138	8368	2
8V3633RA/RJ	HL08-59	121961	187.41	187.90	0.49	0.48	76.3	1.92	229	82	<0.5	<5	12.03	285	18	11	927	6.99	2	0.21	<10	1.22	4611	<2	0.01	2	1045	32900	>5.00	31	2	294	<5	0.07	<10	30	47	516	30300	2
8V3633RA/RJ	HL08-59	121962	187.90	189.90	2.00	0.02	0.1	2.12	12	126	<0.5	<5	5.16	1	18	20	37	5.19	<1	0.38	<10	1.17	2034	<2	0.02	4	1447	78	0.57	5	3	154	<5	0.10	<10	<10	49	<10	164	3
8V3633RA/RJ	HL08-59	121963	189.90	191.90	2.00	0.02	0.3	2.00	9	116	<0.5	<5	5.21	1	17	7	19	4.99	<1	0.34	<10	1.12	1884	<2	0.02	2	1589	172	0.62	5	3	161	<5	0.12	<10	<10	51	<10	177	2
8V3633RA/RJ	HL08-59	121964	191.90	193.90	2.00	0.01	<0.1	2.15	5	126	<0.5	<5	4.43	1	20	8	19	5.33	<1	0.36	<10	1.17	1825	<2	0.02	3	1595	47	0.62	5	3	198	<5	0.13	<10	<10	57	<10	116	3
8V3633RA/RJ	HL08-59	121965	193.90	195.90	2.00	0.01	0.1	1.97	21	129	<0.5	<5	5.22	<1	18	20	16	4.66	<1	0.37	<10	1.05	1991	<2	0.02	4	1611	50	0.52	5	3	294	<5	0.10	<10	<10	45	<10	98	2
8V3633RA/RJ	HL08-59	121966	195.90	197.90	2.00	0.01	0.2	2.13	25	150	<0.5	<5	5.33	<1	18	7	16	5.27	<1	0.34	<10	1.16	2457	<2	0.02	3	1569	31	0.52	5										

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																										
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3671RA/RJ	HL08-60	122008	18.94	20.70	1.76	0.66	2.4	1.84	55	105	<0.5	5	3.77	10	17	19	412	4.90	<1	0.30	<10	0.82	2158	29	0.01	4	1392	43	0.75	<5	4	94	<5	0.01	<10	<10	65	11	673	2
8V3671RA/RJ	HL08-60	122009	20.70	22.06	1.36	0.16	2.4	1.61	138	87	<0.5	6	5.53	7	15	16	260	4.76	<1	0.23	<10	0.77	2704	45	0.01	3	1477	36	1.10	<5	4	103	<5	<0.01	<10	11	73	<10	374	2
8V3671RA/RJ	HL08-60	122010	22.06	22.78	0.72	0.15	19.5	1.00	186	53	<0.5	9	>15.00	146	19	15	1114	5.43	<1	0.15	<10	0.55	4609	23	0.01	2	654	3090	4.49	<5	4	302	<5	<0.01	<10	12	41	238	13800	1
8V3671RA/RJ	HL08-60	122011	22.78	24.10	1.32	0.05	1.7	1.14	60	107	<0.5	8	11.21	5	14	16	139	4.39	<1	0.21	<10	0.69	3900	50	0.01	2	1165	34	0.58	<5	4	207	<5	<0.01	<10	<10	45	<10	396	1
8V3671RA/RJ	HL08-60	122012	24.10	26.10	2.00	0.19	1.8	2.23	34	116	<0.5	5	6.97	3	16	10	227	5.19	<1	0.38	<10	1.32	2627	39	0.01	3	1421	28	0.58	<5	4	200	<5	0.01	<10	<10	56	<10	258	2
8V3671RA/RJ	HL08-60	122013	26.10	28.10	2.00	0.32	2.1	1.82	69	77	<0.5	5	5.93	4	16	10	237	4.31	<1	0.28	<10	1.04	2109	76	0.01	2	1375	28	0.60	<5	3	182	<5	0.02	<10	<10	48	<10	252	2
8V3671RA/RJ	HL08-60	122014	28.10	30.10	2.00	0.17	2.7	2.01	44	85	<0.5	<5	4.82	4	13	11	267	4.75	<1	0.24	<10	1.23	2081	60	0.02	2	1272	30	0.67	<5	4	120	<5	0.01	<10	<10	65	<10	311	2
8V3671RA/RJ	HL08-60	122015	30.10	32.10	2.00	0.09	3.2	2.20	70	107	<0.5	5	2.97	5	16	14	314	6.09	<1	0.24	<10	1.35	2130	48	0.01	3	1392	30	1.26	<5	3	91	<5	<0.01	<10	<10	58	<10	298	2
8V3671RA/RJ	HL08-60	122016	32.10	33.80	1.70	0.12	2.6	2.06	59	90	<0.5	<5	4.24	4	14	14	245	4.88	<1	0.30	<10	1.19	2367	76	0.01	3	1288	28	0.89	<5	3	93	<5	0.04	<10	<10	57	10	314	2
8V3671RA/RJ	HL08-60	122017	33.80	35.19	1.39	0.15	2.7	1.10	93	54	<0.5	<5	11.71	6	11	13	191	3.55	<1	0.17	<10	0.68	3058	29	0.01	3	969	67	1.39	<5	3	197	<5	0.01	<10	<10	33	<10	428	1
8V3671RA/RJ	HL08-60	122018	35.19	37.06	1.87	0.17	2.0	2.10	69	99	<0.5	<5	4.90	5	17	13	223	4.72	<1	0.31	<10	1.10	2439	58	0.01	3	1253	40	0.80	<5	3	85	<5	0.11	<10	<10	57	<10	275	2
8V3671RA/RJ	HL08-60	122019	37.06	38.57	1.51	0.41	3.2	1.39	219	45	<0.5	5	10.06	9	17	95	186	4.44	<1	0.12	<10	0.92	2987	29	0.01	3	1650	73	1.97	<5	7	138	<5	0.05	<10	12	72	<10	309	2
8V3671RA/RJ	HL08-60	122020	38.57	40.12	1.55	2.66	5.4	2.42	212	59	<0.5	5	10.18	9	32	210	193	6.58	<1	0.12	<10	1.81	3074	8	0.01	35	1599	123	2.36	<5	19	181	<5	0.09	<10	<10	169	<10	317	3
8V3671RA/RJ	HL08-60	122021	40.12	41.69	1.57	0.03	0.9	2.26	79	57	<0.5	8	10.55	4	23	173	83	4.98	<1	0.09	<10	1.91	2948	6	0.01	23	1486	51	0.51	<5	17	217	<5	0.01	<10	<10	159	<10	128	2
8V3671RA/RJ	HL08-60	122022	41.69	43.27	1.58	0.05	0.2	2.24	59	46	<0.5	<5	14.79	3	27	224	76	4.73	<1	0.05	<10	2.03	3589	<2	0.01	29	1573	35	0.59	<5	17	215	<5	0.08	<10	11	172	<10	80	3
8V3671RA/RJ	HL08-60	122023	43.27	44.53	1.26	0.01	0.8	2.56	49	44	<0.5	<5	6.56	4	33	243	111	5.52	<1	0.05	<10	2.33	1802	<2	0.01	34	1987	46	0.60	<5	11	129	<5	0.16	<10	<10	183	<10	100	4
8V3671RA/RJ	HL08-60	122024	44.53	46.35	1.82	0.02	0.6	2.73	48	50	<0.5	<5	10.58	4	31	260	99	5.35	1	0.06	<10	2.40	3341	3	0.01	36	1860	47	0.35	<5	19	263	<5	0.12	<10	13	189	<10	219	5
8V3671RA/RJ	HL08-60	122025	Std	PM1116		0.14	784.8	0.67	575	177	<0.5	108	0.55	22	6	22	7593	2.19	6	0.15	<10	0.57	272	551	0.03	5	462	865	1.11	1714	2	77	<5	0.06	<10	<10	18	<10	816	2
8V3671RA/RJ	HL08-60	122026	46.35	47.37	1.02	0.01	1.1	1.65	40	52	<0.5	8	11.41	12	25	166	73	4.83	<1	0.12	<10	1.77	3290	9	0.01	30	1543	1336	0.76	<5	15	332	<5	0.01	<10	14	108	20	1055	2
8V3671RA/RJ	HL08-60	122027	47.37	48.90	1.53	0.01	<0.1	2.60	17	215	<0.5	<5	10.49	2	24	233	8	4.67	<1	0.06	<10	2.63	2794	4	0.01	31	1654	39	0.16	<5	15	290	<5	0.09	<10	<10	146	<10	111	7
8V3671RA/RJ	HL08-60	122028	48.90	50.44	1.54	0.01	0.2	2.65	34	166	<0.5	<5	8.98	6	30	259	104	4.66	<1	0.04	<10	2.77	2997	<2	0.01	34	1916	61	0.23	<5	13	208	<5	0.11	<10	<10	170	<10	446	6
8V3671RA/RJ	HL08-60	122029	50.44	52.44	2.00	0.01	0.4	2.46	35	83	<0.5	<5	5.28	3	20	134	30	5.11	<1	0.15	<10	2.02	1954	<2	0.02	17	1617	58	0.37	<5	12	140	<5	0.09	<10	<10	133	<10	124	4
8V3671RA/RJ	HL08-60	122030	52.44	54.44	2.00	<0.01	<0.1	2.69	43	209	<0.5	5	11.73	3	28	208	19	5.97	<1	0.13	<10	2.28	2639	<2	0.01	33	1764	23	0.33	<5	16	339	<5	0.06	<10	<10	157	<10	104	6
8V3671RA/RJ	HL08-60	122031	54.44	56.40	1.96	0.01	0.9	2.06	47	48	<0.5	<5	9.52	10	29	232	115	4.43	<1	0.05	<10	1.89	2430	2	0.01	31	1823	256	0.41	<5	12	220	<5	0.14	<10	<10	158	13	725	8
8V3671RA/RJ	HL08-60	122032	56.40	58.40	2.00	0.01	2.0	2.13	42	48	<0.5	<5	6.47	22	29	188	148	4.69	<1	0.05	<10	2.04	2102	<2	0.01	32	1929	1303	0.79	<5	8	134	<5	0.13	<10	<10	143	34	2011	5
8V3671RA/RJ	HL08-60	122033	58.40	60.40	2.00	0.02	0.6	2.02	35	73	<0.5	<5	5.59	13	26	208	46	3.84	<1	0.09	<10	2.23	1541	3	0.03	33	2031	366	0.31	<5	8	113	<5	0.18	<10	<10	155	22	1245	5
8V3671RA/RJ	HL08-60	122034	60.40	62.40	2.00	0.06	2.0	2.42	212	34	<0.5	8	14.46	12	27	218	121	6.52	3	0.04	<10	2.02	4281	2	0.01	30	1403	201	1.60	<5	18	267	<5	0.04	<10	18	171	12	665	5
8V3671RA/RJ	HL08-60	122035	62.40	64.40	2.00	0.02	0.3	2.36	90	57	<0.5	<5	10.66	4	32	258	68	5.20	2	0.06	<10	2.02	2495	<2	0.02	37	1911	22	0.46	<5	16	182	<5	0.13	<10	<10	194	<10	92	9
8V3671RA/RJ	HL08-60	122036	64.40	66.40	2.00	0.03	1.0	2.41	117	34	<0.5	<5	13.23	5	33	229	113	5.63	1	0.03	<10	2.28	2989	10	0.01	36	1704	27	0.91	<5	15	237	<5	0.08	<10	<10	184	<10	94	5
8V3671RA/RJ	HL08-60	122037	66.40	68.40	2.00	0.01	0.4	2.30	65	39	<0.5	<5	12.81	3	35	239	138	4.83	1	0.04	<10	2.29	2533	3	0.02	36	1872	22	0.49	<5	12	221	<5	0.11	<10	<10	167	<10	79	

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																											
					Inter (m)	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3671RA/RJ	HL08-60	122080	135.90	137.90	2.00	<0.01	<0.1	2.75	<5	98	<0.5	<5	4.37	1	20	11	51	5.69	1	0.31	<10	1.74	2034	<2	0.03	3	1468	22	0.13	<5	5	136	<5	0.12	<10	<10	81	<10	97	3
8V3671RA/RJ	HL08-60	122081	137.90	139.03	1.13	0.06	1.2	2.32	14	71	<0.5	<5	3.98	2	19	14	118	5.19	1	0.24	<10	1.35	2249	21	0.02	3	1496	149	0.39	<5	4	106	<5	0.12	<10	<10	60	<10	156	4
8V3671RA/RJ	HL08-60	122082	139.03	140.28	1.25	<0.01	<0.1	2.58	8	100	<0.5	<5	3.50	1	24	6	71	5.59	1	0.33	<10	1.57	1966	<2	0.02	4	1676	35	0.39	<5	5	105	<5	0.14	<10	<10	80	<10	92	3
8V3671RA/RJ	HL08-60	122083	140.28	141.77	1.49	0.02	0.2	2.25	15	190	<0.5	<5	3.00	1	21	9	73	5.34	<1	0.31	<10	1.33	1943	<2	0.02	4	1708	25	0.61	<5	3	79	<5	0.11	<10	<10	61	<10	84	3
8V3671RA/RJ	HL08-60	122084	141.77	143.52	1.75	<0.01	0.2	2.56	7	126	<0.5	<5	3.34	1	24	5	88	5.73	<1	0.39	<10	1.43	1927	<2	0.03	4	1642	23	0.49	<5	5	103	<5	0.15	<10	<10	73	<10	93	3
8V3671RA/RJ	HL08-60	122085	143.52	144.82	1.30	0.09	0.3	2.74	19	133	<0.5	<5	4.33	2	26	21	67	6.35	<1	0.26	<10	1.61	2190	<2	0.01	6	1717	74	0.63	<5	4	130	<5	0.10	<10	12	68	<10	91	3
8V3671RA/RJ	HL08-60	122086	144.82	146.30	1.48	0.08	0.5	2.43	123	100	<0.5	<5	4.45	4	22	7	70	6.00	<1	0.36	<10	1.31	2371	<2	0.01	3	1636	46	1.14	<5	3	121	<5	0.08	<10	<10	68	<10	100	3
8V3671RA/RJ	HL08-60	122087	146.30	147.80	1.50	0.07	0.9	2.04	1516	76	<0.5	<5	5.02	37	19	8	85	5.56	<1	0.28	<10	1.09	2070	<2	0.01	3	1568	96	1.30	<5	3	130	<5	0.04	<10	<10	58	<10	261	2
8V3671RA/RJ	HL08-60	122088	147.80	149.80	2.00	0.01	0.3	2.46	40	105	<0.5	<5	4.50	2	19	9	64	5.90	<1	0.34	<10	1.27	2343	<2	0.01	3	1654	28	0.63	<5	3	133	<5	0.07	<10	<10	77	<10	119	2
8V3671RA/RJ	HL08-60	122089	149.80	151.80	2.00	0.01	0.6	2.44	84	144	<0.5	<5	5.06	3	20	11	66	5.35	<1	0.43	<10	1.22	2435	<2	0.01	4	1619	70	0.70	<5	4	157	<5	0.03	<10	<10	72	<10	128	2
8V3671RA/RJ	HL08-60	122090	151.80	152.63	0.83	0.04	0.9	2.15	109	111	<0.5	6	3.67	6	17	8	68	5.81	<1	0.32	<10	1.06	1992	<2	0.01	3	1506	59	1.31	<5	3	114	<5	0.01	<10	<10	64	<10	231	2
8V3671RA/RJ	HL08-60	122091	152.63	154.18	1.55	0.02	0.4	2.70	323	133	<0.5	7	4.67	9	19	9	51	6.39	<1	0.41	<10	1.46	2420	<2	0.02	3	1608	29	0.64	<5	4	188	<5	<0.01	<10	<10	75	<10	99	2
8V3671RA/RJ	HL08-60	122092	154.18	155.70	1.52	0.15	1.2	2.08	346	106	<0.5	6	3.98	10	19	11	89	6.43	<1	0.33	<10	1.08	1718	<2	0.01	4	1596	56	2.08	<5	3	130	<5	<0.01	<10	<10	54	<10	159	2
8V3671RA/RJ	HL08-60	122093	155.70	157.32	1.62	0.02	3.4	1.58	200	130	<0.5	5	3.99	27	15	8	158	3.96	<1	0.39	<10	0.95	1918	<2	0.02	3	1464	2567	0.67	<5	3	174	<5	<0.01	<10	<10	38	33	2100	1
8V3671RA/RJ	HL08-60	122094	157.32	159.32	2.00	0.01	0.3	2.32	101	122	<0.5	6	3.24	3	16	8	46	6.15	<1	0.33	<10	1.21	2059	<2	0.02	3	1554	28	0.71	<5	3	142	<5	0.01	<10	<10	64	<10	104	2
8V3671RA/RJ	HL08-60	122095	159.32	161.32	2.00	0.01	<0.1	2.88	22	115	<0.5	5	4.00	2	19	6	34	6.85	<1	0.36	<10	1.60	1793	<2	0.03	3	1612	28	0.48	<5	5	167	<5	0.03	<10	<10	82	<10	89	3
8V3671RA/RJ	HL08-60	122096	161.32	162.80	1.48	<0.01	<0.1	2.11	15	80	<0.5	5	5.11	2	13	9	21	4.82	<1	0.29	<10	1.22	1831	<2	0.02	2	1353	46	0.48	<5	3	179	<5	0.01	<10	<10	49	<10	144	2
8V3671RA/RJ	HL08-60	122097	162.80	164.30	1.50	0.12	0.1	2.03	1294	83	<0.5	7	9.03	32	14	8	43	5.08	<1	0.29	<10	1.20	3171	<2	0.01	2	1180	25	0.78	<5	3	237	<5	<0.01	<10	12	46	<10	78	2
8V3671RA/RJ	HL08-60	122098	164.30	166.30	2.00	<0.01	<0.1	2.09	23	96	<0.5	5	5.37	1	15	9	23	4.69	<1	0.25	<10	1.60	1615	<2	0.03	3	1414	14	0.37	<5	3	239	<5	0.02	<10	<10	63	<10	42	2
8V3671RA/RJ	HL08-60	122099	166.30	168.30	2.00	0.01	<0.1	2.35	25	133	<0.5	5	4.77	2	17	9	33	4.80	<1	0.38	<10	1.62	1671	<2	0.02	3	1450	19	0.44	<5	4	191	<5	0.02	<10	<10	65	<10	43	2
8V3671RA/RJ	HL08-60	122100	Blank	Blank	<0.01	<0.1	0.07	<5	<10	<0.5	8	>15.00	1	1	11	7	0	10	<1	0.02	<10	4.38	106	<2	0.01	1	132	<2	0.03	<5	<1	3810	<5	<0.01	<10	<10	2	<10	71	<1
8V3671RA/RJ	HL08-60	122101	168.30	170.30	2.00	0.01	0.5	2.02	32	115	<0.5	<5	5.95	1	17	7	36	4.78	<1	0.41	<10	1.07	1876	<2	0.02	3	1395	20	0.66	<5	4	178	<5	0.07	<10	<10	71	<10	54	2
8V3671RA/RJ	HL08-60	122102	170.30	172.30	2.00	0.01	0.3	2.40	12	81	<0.5	<5	5.80	1	17	6	40	5.49	<1	0.27	<10	1.72	1696	<2	0.02	2	1367	18	0.22	<5	5	342	<5	0.04	<10	<10	80	<10	80	3
8V3671RA/RJ	HL08-60	122103	172.30	174.26	1.96	0.01	0.1	2.31	8	92	<0.5	<5	4.62	1	17	7	37	4.71	<1	0.36	<10	1.53	1579	<2	0.03	2	1412	19	0.27	<5	4	193	<5	0.12	<10	<10	69	<10	68	3
8V3671RA/RJ	HL08-60	122104	174.26	175.76	1.50	0.04	0.6	1.58	23	113	<0.5	<5	4.12	2	18	11	48	3.33	<1	0.35	<10	0.97	1408	<2	0.01	3	1449	175	0.44	<5	3	165	<5	0.14	<10	<10	47	<10	126	2
8V3671RA/RJ	HL08-60	122105	175.76	177.25	1.49	0.01	0.2	2.55	19	143	<0.5	<5	3.64	2	22	6	30	6.13	<1	0.41	<10	1.32	2281	<2	0.02	3	1534	21	0.40	<5	7	137	<5	0.17	<10	<10	95	<10	131	4
8V3671RA/RJ	HL08-60	122106	177.25	178.75	1.50	0.02	0.1	1.54	21	102	<0.5	<5	3.78	1	23	7	22	3.36	<1	0.39	<10	0.77	1510	4	0.01	5	1486	13	0.21	<5	2	137	<5	0.09	<10	<10	39	<10	73	2
8V3671RA/RJ	HL08-60	122107	178.75	180.75	2.00	0.01	0.2	2.21	19	109	<0.5	<5	4.82	1	19	8	8	4.81	<1	0.55	<10	1.00	2151	<2	0.01	3	1446	17	0.44	<5	3	190	<5	0.15	<10	<10	48	<10	78	3
8V3671RA/RJ	HL08-60	122108	180.75	181.20	0.45	0.02	1.5	1.47	49	100	<0.5	<5	4.25	6	19	13	50	3.59	<1	0.42	<10	0.62	1941	<2	0.01	3	1465	99	0.64	<5	3	164	<5	0.10	<10	<10	33	10	685	2
8V3671RA/RJ	HL08-60	122109	181.20	182.52	1.32	0.01	0.4	2.14	29	115	<0.5	<5	4.41	2	20	7	41	5.01	<1	0.48	<10	1.03	2070	<2	0.01	3	1459	19	0.64	<5	3	160	<5	0.05	<10	<10	59	<10	98	2
8V3671RA/RJ	HL08-60	122110	182.52	184.52	2.00	0.01	0.3	2.00	18	107	<0.5	<5	4.61	1	16	8	26	4.47	<1	0.41	<10	1.04	1908	<2	0.01	3	1500	17	0.48	<5	3	182	<5	0.02	<10	<10	52	<10	84	2
8V3671RA/RJ	HL08-60	122111	184.52	186.24	1.72	0.02	0.3	2.09	68	159	<0.5	<5	7.07	3	16	10	29	4.05	<1	0.66	<10	0.79	2240	<2	0.05	3	1252	42	1.17	<5	3	178	<5	0.10	<10	<10	50	<10	89	2
8V3671RA/RJ	HL08-60	122112	186.24	188.10	1.86	0.01	0.5	2.64	75	83	<0.5	<5	4.72	3	22	14	77	4.97	<1	0.25	<10	1.24	1728	<2	0.13	3	1421	34	0.79	<5	5	164	<5	0.14	<10	<10	95	<10	130	3
8V3671RA/RJ	HL08-60	122113	199.42	200.88	1.46	0.01	0.3	2.55	176	79	<0.5	<5	6.41	5																										

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0 1.0-3.0 3.0-5.0 >5.0				Ag: 5-10 10-50 50-100 >100				Pb/Zn: 2500-5000 5000-10000 >10000																										
						Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3699RA/RJ	HLO8-61	122314	20.80	22.30	1.50	0.01	0.6	0.81	22	188	<0.5	<5	2.83	2	13	28	31	2.95	<1	0.38	<10	0.48	940	<2	0.02	3	1340	14	0.51	<5	3	127	<5	<0.01	<10	<10	12	<10	159	2
8V3699RA/RJ	HLO8-61	122315	22.30	23.80	1.50	0.05	0.5	0.48	22	154	<0.5	8	8.60	1	11	27	8	4.74	<1	0.32	<10	1.53	2578	<2	0.02	2	1157	9	0.50	<5	3	589	<5	<0.01	<10	<10	10	<10	74	2
8V3699RA/RJ	HLO8-61	122316	23.80	25.30	1.50	0.05	0.6	1.29	54	169	<0.5	6	4.52	2	12	15	24	4.12	<1	0.32	<10	1.00	1776	<2	0.02	3	1235	12	0.69	<5	4	205	<5	<0.01	<10	<10	25	<10	70	2
8V3699RA/RJ	HLO8-61	122317	25.30	27.30	2.00	0.04	0.5	1.51	55	218	<0.5	5	2.55	2	14	12	22	4.19	<1	0.39	<10	1.05	1404	<2	0.02	4	1298	16	0.73	<5	4	121	<5	<0.01	<10	<10	27	<10	76	2
8V3699RA/RJ	HLO8-61	122318	27.30	29.30	2.00	0.05	0.6	1.81	75	207	<0.5	5	2.94	3	14	13	19	3.99	<1	0.32	<10	1.07	1572	<2	0.03	4	1287	19	0.49	<5	4	166	<5	0.01	<10	<10	40	<10	80	2
8V3699RA/RJ	HLO8-61	122319	29.30	31.30	2.00	0.04	0.6	1.79	95	206	<0.5	<5	1.91	3	15	9	27	4.31	<1	0.31	<10	1.11	1413	<2	0.04	3	1381	15	0.72	<5	3	97	<5	0.04	<10	<10	43	<10	90	3
8V3699RA/RJ	HLO8-61	122320	31.30	33.30	2.00	0.14	0.8	1.44	171	184	<0.5	<5	2.61	5	14	9	26	4.01	<1	0.28	<10	0.89	1300	<2	0.03	2	1316	41	1.12	<5	3	133	<5	0.03	<10	<10	35	<10	99	3
8V3699RA/RJ	HLO8-61	122321	33.30	35.30	2.00	0.13	0.7	1.56	127	200	<0.5	<5	1.99	4	15	8	24	3.80	<1	0.33	<10	0.96	1188	<2	0.03	2	1330	41	0.82	<5	3	81	<5	0.07	<10	<10	35	<10	121	3
8V3699RA/RJ	HLO8-61	122322	35.30	37.30	2.00	0.02	0.5	1.33	57	229	<0.5	<5	2.32	2	15	8	29	3.41	<1	0.31	<10	0.77	1138	<2	0.02	2	1283	13	0.92	<5	2	86	<5	0.03	<10	<10	29	<10	73	2
8V3699RA/RJ	HLO8-61	122323	37.30	39.30	2.00	0.01	0.5	1.44	54	218	<0.5	<5	2.82	2	14	6	23	3.88	<1	0.38	<10	0.69	1305	<2	0.02	2	1290	14	1.12	<5	2	114	<5	0.04	<10	<10	31	<10	74	2
8V3699RA/RJ	HLO8-61	122324	39.30	40.60	1.30	<0.01	0.4	1.50	17	197	<0.5	<5	3.64	1	14	7	24	3.79	<1	0.35	<10	0.69	1446	<2	0.02	2	1258	13	0.66	<5	3	170	<5	0.08	<10	<10	32	<10	60	3
8V3699RA/RJ	HLO8-61	122325	Blank	Blank	<0.01	<0.1	0.10	<5	24	<0.5	9	>15.00	<1	1	6	2	0.09	1	0.05	<10	2.21	54	<2	0.01	<1	86	<2	0.05	<5	<1	4139	<5	<0.01	<10	<10	2	<10	1	<1	
8V3699RA/RJ	HLO8-61	122326	40.30	42.30	2.00	0.01	0.5	1.40	61	176	<0.5	<5	2.59	2	16	9	29	3.62	<1	0.29	<10	0.74	1245	<2	0.02	2	1224	15	0.61	<5	2	93	<5	0.07	<10	<10	38	<10	57	2
8V3699RA/RJ	HLO8-61	122327	42.30	44.13	1.83	0.01	0.5	1.60	56	230	<0.5	<5	2.96	2	14	7	17	4.12	<1	0.36	<10	0.85	1241	<2	0.02	2	1263	18	0.89	<5	2	133	<5	0.09	<10	<10	32	<10	69	3
8V3699RA/RJ	HLO8-61	122328	44.13	46.13	2.00	<0.01	0.4	1.46	16	229	<0.5	<5	3.85	2	14	14	17	3.89	<1	0.25	<10	0.83	1244	<2	0.03	2	1251	70	0.57	<5	3	183	<5	0.08	<10	<10	41	<10	132	3
8V3699RA/RJ	HLO8-61	122329	46.13	48.13	2.00	0.11	1.2	1.52	127	220	<0.5	<5	3.87	5	15	7	26	4.37	<1	0.31	<10	0.77	1421	<2	0.04	2	1256	168	1.25	<5	3	186	<5	0.10	<10	<10	43	<10	297	3
8V3699RA/RJ	HLO8-61	122330	48.13	50.13	2.00	0.03	0.5	1.70	24	213	<0.5	<5	3.33	1	17	8	24	4.33	<1	0.31	10	0.86	1407	<2	0.03	2	1283	26	0.53	<5	3	135	<5	0.13	<10	<10	41	<10	85	3
8V3699RA/RJ	HLO8-61	122331	50.13	52.13	2.00	0.03	0.7	1.57	47	207	<0.5	<5	2.78	2	15	7	26	4.18	<1	0.33	<10	0.74	1464	<2	0.03	2	1217	16	0.84	<5	3	119	<5	0.09	<10	<10	35	<10	82	3
8V3699RA/RJ	HLO8-61	122332	52.13	54.13	2.00	0.04	0.7	1.66	40	180	<0.5	<5	1.27	2	14	10	28	4.48	<1	0.30	10	0.80	1266	<2	0.02	2	1199	19	0.77	<5	3	55	<5	0.02	<10	<10	36	<10	170	2
8V3699RA/RJ	HLO8-61	122333	54.13	56.10	1.97	0.20	2.2	1.35	332	156	<0.5	<5	0.83	9	16	7	28	4.60	<1	0.37	10	0.59	928	<2	0.02	3	1131	37	2.23	<5	2	35	<5	0.04	<10	<10	24	<10	131	3
8V3699RA/RJ	HLO8-61	122334	56.10	58.10	2.00	0.22	2.3	1.22	273	170	<0.5	<5	1.61	7	15	11	32	3.94	<1	0.32	<10	0.60	1123	<2	0.02	3	1063	35	1.83	<5	2	56	<5	0.06	<10	<10	21	<10	90	3
8V3699RA/RJ	HLO8-61	122335	58.10	60.10	2.00	0.08	0.7	1.53	136	222	<0.5	<5	3.52	4	15	6	21	3.78	<1	0.38	11	0.74	1628	<2	0.02	2	1211	21	0.91	<5	3	120	<5	0.10	<10	<10	27	<10	88	3
8V3699RA/RJ	HLO8-61	122336	60.10	62.10	2.00	0.02	0.9	1.54	11	187	<0.5	<5	3.31	1	16	7	21	3.68	<1	0.32	10	0.75	1410	<2	0.02	2	1232	11	0.35	<5	3	127	<5	0.10	<10	<10	26	<10	87	3
8V3699RA/RJ	HLO8-61	122337	62.10	64.10	2.00	0.01	0.2	1.61	<5	748	<0.5	<5	4.96	1	14	5	18	3.36	<1	0.35	<10	0.80	1540	<2	0.02	2	1185	10	0.10	<5	3	214	<5	0.08	<10	<10	27	<10	87	3
8V3699RA/RJ	HLO8-61	122338	64.10	65.41	1.31	0.06	0.8	1.48	108	149	<0.5	<5	2.05	3	15	10	24	4.37	<1	0.27	<10	0.70	1136	<2	0.02	3	946	20	1.38	<5	2	62	<5	0.04	<10	<10	24	<10	110	2
8V3699RA/RJ	HLO8-61	122339	65.41	66.90	1.49	0.04	0.9	1.73	67	219	<0.5	<5	0.78	2	15	7	26	4.52	<1	0.33	<10	0.84	987	<2	0.02	2	1159	30	1.20	<5	3	34	<5	0.02	<10	<10	29	<10	105	3
8V3699RA/RJ	HLO8-61	122340	66.90	68.40	1.50	0.13	1.6	1.57	250	156	<0.5	<5	0.95	7	17	12	28	4.66	<1	0.30	<10	0.81	994	<2	0.02	4	1162	24	1.84	<5	3	34	<5	0.06	<10	<10	31	<10	64	3
8V3699RA/RJ	HLO8-61	122341	68.40	69.90	1.50	0.06	2.2	2.34	203	169	<0.5	5	1.10	6	20	11	36	5.70	<2	0.29	<10	1.18	1329	<2	0.02	7	1234	26	1.52	<5	3	39	<5	0.04	<10	<10	43	<10	76	3
8V3699RA/RJ	HLO8-61	122342	69.90	71.40	1.50	0.03	1.3	2.06	138	174	<0.5	5	1.36	4	16	14	29	4.80	<1	0.27	<10	1.03	1296	<2	0.02	6	1398	18	1.00	<5	3	49	<5	0.02	<10	<10	38	<10	71	3
8V3699RA/RJ	HLO8-61	122343	71.40	72.90	1.50	0.08	2.1	1.99	132	206	<0.5	7	0.55	5	18	11	25	4.94	<1	0.32	<10	1.01	1005	<2	0.02	7	1282	38	1.53	<5	3	35	<5	0.01	<10	<10	34	<10	93	3
8V3699RA/RJ	HLO8-61	122344	72.90	74.40	1.50	0.02	1.3	2.11	69	201	<0.5	8	2.46	3	21	13	40	5.49	<1	0.30	<10	1.01	1346	<2	0.02	7	1385	23	1.73	<5	3	82	<5	0.01	<10	<10	39	<10	76	3
8V3699RA/RJ	HLO8-61	122345	74.40	75.90	1.50	0.09	2.0	1.90	130	193	<0.5	7	0.99	4	18	8	38	4.87	<1	0.31	<10	0.88	1002	<2	0.02	5	1377	31	1.59	<5	3	43	<5	0.01	<10	<10	31	<10	82	3
8V3699RA/RJ	HLO8-61	122346	75.90	77.40	1.50	0.39	6.2	2.33	390	180	<0.5	7	0.75	12	19	13	36	6.23	<1	0.27	<10	1.23	1175	<2	0.02	5	1619	61	2.06	<5	3	37	<5	0.02	<10	<10	41	<10	222	3
8V3699RA/RJ	HLO8-61	122347	77.40	78.90	1.50	0.08	2.5	2.32	340	177	<0.5	6	1.25	10	17	11	27	5.41	<1	0.28	<10	1.22	1293	<2	0.02	2	1433	44	1.26	<5										

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																											
						0.5-1.0	1.0-3.0	3.0-5.0	>5.0	5-10	10-50	50-100	>100	2500-5000	5000-10000	>10000	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Zr													
8V3699RA/RJ	HL08-61	122383	137.50	139.50	2.00	0.05	1.4	2.47	144	201	<0.5	<5	3.01	5	21	9	33	5.96	1	0.34	<10	1.43	1427	<2	0.02	3	1728	97	1.95	<5	4	91	<5	0.07	<10	<10	48	<10	99	3	
8V3699RA/RJ	HL08-61	122384	139.50	141.46	1.96	0.15	3.1	2.37	265	193	<0.5	5	4.70	8	22	10	67	6.42	<1	0.37	<10	1.25	1734	<2	0.02	3	1656	126	3.10	<5	4	146	<5	0.05	<10	<10	45	<10	159	3	
8V3699RA/RJ	HL08-61	122385	141.46	143.46	2.00	<0.01	0.7	3.33	18	177	<0.5	7	2.27	2	21	11	16	6.74	1	0.29	<10	1.77	1755	<2	0.02	3	1653	30	0.37	<5	5	77	<5	0.02	<10	<10	40	<10	118	3	
8V3699RA/RJ	HL08-61	122386	143.46	145.46	2.00	0.02	1.2	3.15	36	199	<0.5	9	3.66	2	20	9	27	6.56	<1	0.33	11	1.59	1952	<2	0.01	3	1702	94	0.64	<5	4	128	<5	0.01	<10	<10	48	<10	114	3	
8V3699RA/RJ	HL08-61	122387	145.46	147.46	2.00	0.02	0.7	3.10	18	199	<0.5	5	5.31	1	22	8	10	6.10	<1	0.31	10	1.74	2187	<2	0.01	3	1630	25	0.51	<5	5	172	<5	0.03	<10	<10	45	<10	91	3	
8V3699RA/RJ	HL08-61	122388	147.46	149.46	2.00	0.02	0.7	3.02	40	197	<0.5	8	5.14	2	21	8	15	6.18	1	0.33	10	1.64	2096	<2	0.02	3	1684	23	0.78	<5	4	156	<5	0.02	<10	<10	42	<10	95	3	
8V3699RA/RJ	HL08-61	122389	149.46	151.46	2.00	0.02	0.8	2.91	51	190	<0.5	8	4.31	2	21	9	18	6.18	<1	0.34	10	1.51	1909	<2	0.02	3	1719	23	0.92	<5	4	155	<5	0.01	<10	<10	46	<10	100	3	
8V3699RA/RJ	HL08-61	122390	151.46	153.46	2.00	0.01	0.6	2.88	11	243	<0.5	7	5.59	1	20	6	17	5.65	<1	0.40	11	1.50	1937	<2	0.02	3	1699	35	0.45	<5	4	225	<5	0.01	<10	<10	47	<10	128	3	
8V3699RA/RJ	HL08-61	122391	153.46	155.46	2.00	0.01	0.6	3.03	16	184	<0.5	7	5.42	1	19	7	17	6.10	<1	0.31	11	1.62	1947	<2	0.02	3	1749	24	0.40	<5	4	192	<5	0.01	<10	<10	49	<10	105	3	
8V3699RA/RJ	HL08-61	122392	155.46	157.46	2.00	0.17	2.1	2.30	94	181	<0.5	6	4.92	3	16	10	27	5.30	<1	0.33	<10	1.14	1966	<2	0.02	2	1533	58	1.44	<5	4	198	<5	0.01	<10	<10	42	<10	95	2	
8V3699RA/RJ	HL08-61	122393	157.46	159.16	1.70	0.28	2.1	2.36	86	181	<0.5	7	2.43	3	19	11	31	6.08	<1	0.34	10	1.20	1719	<2	0.02	3	1693	43	2.25	<5	3	81	<5	0.01	<10	<10	46	<10	137	3	
8V3699RA/RJ	HL08-61	122394	159.16	160.40	1.24	0.02	2.7	0.60	12	66	<0.5	6	14.63	1	4	72	8	1.35	<1	0.13	<10	0.29	4384	<2	0.01	1	448	<2	0.23	<5	2	1062	<5	<0.01	<10	<10	40	<10	21	<1	
8V3699RA/RJ	HL08-61	122395	160.40	161.77	1.37	0.06	3.1	2.01	312	140	<0.5	7	8.81	8	18	14	26	4.55	<1	0.27	<10	1.02	3104	<2	0.02	3	1211	26	1.34	<5	3	615	<5	<0.01	<10	<10	40	<10	74	1	
8V3699RA/RJ	HL08-61	122396	161.77	163.30	1.53	0.12	4.7	2.43	506	98	<0.5	9	3.19	16	33	13	52	7.68	<1	0.35	<10	1.52	1863	<2	0.03	5	1907	77	>5.00	<5	4	123	<5	0.01	<10	<10	66	<10	346	4	
8V3699RA/RJ	HL08-61	122397	163.30	164.30	1.00	0.08	3.5	1.87	330	68	<0.5	9	4.51	12	31	27	54	7.23	<1	0.39	<10	1.08	1874	<2	0.03	6	1899	205	>5.00	<5	4	144	<5	0.01	<10	<10	47	<10	255	3	
8V3699RA/RJ	HL08-61	122398	164.30	165.30	1.00	4.23	8.3	1.18	344	164	<0.5	7	5.61	10	20	17	38	4.70	<1	0.33	<10	1.08	1874	<2	0.02	4	1214	58	3.87	<5	3	199	<5	0.01	<10	<10	31	<10	104	2	
8V3699RA/RJ	HL08-61	122399	165.30	166.30	1.00	1.94	11.7	1.68	1733	160	<0.5	8	7.27	46	25	31	64	6.56	<1	0.37	<10	0.99	2388	<2	0.03	4	1370	131	4.68	<5	4	237	<5	0.01	<10	<10	13	45	<10	275	3
8V3699RA/RJ	HL08-61	122400	Blank	Blank	<0.01	<0.1	0.08	9	23	<0.5	12	>15.00	1	1	8	2	0.08	<1	0.03	<10	2.08	59	<2	0.01	<1	85	<2	0.06	<5	<1	4626	<5	<0.01	<10	12	2	<10	6	<1		
8V3699RA/RJ	HL08-61	122401	166.30	167.30	1.00	2.71	17.0	2.09	382	190	<0.5	5	6.26	12	25	20	55	5.00	<1	0.32	<10	1.30	2263	<2	0.03	3	1661	126	2.54	<5	5	176	<5	0.06	<10	<10	58	<10	387	3	
8V3699RA/RJ	HL08-61	122402	167.30	168.50	1.20	5.71	6.4	2.36	473	204	<0.5	6	5.18	13	24	11	59	5.82	<1	0.34	<10	1.33	1997	<2	0.04	3	1677	75	1.82	<5	5	146	<5	0.03	<10	12	68	<10	121	3	
8V3699RA/RJ	HL08-61	122403	168.50	170.30	1.80	0.05	2.9	2.57	128	208	<0.5	6	5.24	5	22	11	51	6.14	<1	0.26	<10	1.45	2028	<2	0.03	3	1517	124	1.48	<5	4	166	<5	0.02	<10	12	73	<10	205	3	
8V3699RA/RJ	HL08-61	122404	170.30	171.80	1.50	0.05	3.0	2.78	105	215	<0.5	7	5.15	4	25	11	54	6.67	<1	0.35	<10	1.83	2366	<2	0.03	3	1754	127	1.40	<5	5	154	<5	0.02	<10	12	90	<10	114	3	
8V3699RA/RJ	HL08-61	122405	171.80	173.31	1.51	0.03	2.1	2.16	194	215	<0.5	6	4.18	6	20	21	37	5.56	<1	0.34	<10	1.27	1648	<2	0.02	2	1534	53	1.44	<5	5	121	<5	0.01	<10	<10	59	<10	152	3	
8V3699RA/RJ	HL08-61	122406	173.31	174.80	1.49	0.02	3.3	2.62	226	249	<0.5	6	5.65	7	31	10	62	6.83	<1	0.42	<10	1.68	1994	<2	0.03	3	2027	100	2.43	<5	6	164	<5	0.04	<10	16	82	<10	139	3	
8V3699RA/RJ	HL08-61	122407	174.80	176.30	1.50	0.02	4.0	3.14	161	186	<0.5	<5	3.82	5	35	10	82	7.25	<1	0.31	<10	2.34	2420	<2	0.02	4	1839	57	1.14	<5	6	110	<5	0.07	<10	17	100	<10	179	3	
8V3699RA/RJ	HL08-61	122408	176.30	177.80	1.50	0.21	15.1	3.27	147	199	<0.5	8	4.04	7	39	9	99	7.63	<1	0.34	<10	2.31	2691	<2	0.03	7	1805	141	1.33	<5	6	128	<5	0.01	<10	17	112	<10	382	3	
8V3699RA/RJ	HL08-61	122409	177.80	179.30	1.50	0.03	3.1	3.02	118	178	<0.5	6	3.67	4	41	8	74	6.94	<1	0.30	<10	2.15	2787	<2	0.03	8	1784	52	0.89	<5	5	113	<5	0.05	<10	17	91	<10	137	3	
8V3699RA/RJ	HL08-61	122410	179.30	181.30	1.80	0.02	4.1	2.84	94	242	<0.5	<5	2.45	3	36	9	73	6.40	<1	0.40	<10	1.89	2590	<2	0.03	8	2071	55	0.83	<5	5	76	<5	0.07	<10	<10	82	<10	132	3	
HL08-62 - Zone: Hammer, Pad 40: 435043E,6223824N, Elev: 1218m, Az: 093, Dip: -70, EOH: 206.10m																																									
8V3633RA/RJ	HL08-62	122138	1.13	2.95	1.82	0.03	0.5	0.34	37	165	<0.5	<5	3.93	1	8	81	3	2.99	<1	0.23	<10	0.80	1561	<2	0.01	3	971	19	0.42	<5	2	227	<5	<0.01	<10	<10	9	<10	70	1	
8V3633RA/RJ	HL08-62	122139	2.95	4.45	1.50	0.05	0.4	0.61	104	214	<0.5	<5	3.06	2	16	23	24	4.28	<1	0.33	<10	0.77	1311	<2	0.02	3	1368	25	1.59	<5	4	179	<5	<0.01	<10	<10	13	<10	63		

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn:																											
					0.5-1.0	1.0-3.0	3.0-5.0	>5.0	5-10	10-50	50-100	>100	2500-5000	5000-10000	>10000	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Zr													
8V3671RA/RJ	HL08-62	122181	71.05	72.55	1.50	0.01	0.2	1.78	26	126	<0.5	<5	3.52	1	14	12	22	3.66	<1	0.27	10	0.97	1648	<2	0.02	3	1327	12	0.35	<5	3	116	<5	0.08	<10	<10	33	<10	78	2
8V3671RA/RJ	HL08-62	122182	72.55	73.84	1.29	0.02	0.3	1.90	28	112	<0.5	<5	3.22	2	16	14	21	4.29	<1	0.24	11	0.99	1545	<2	0.03	3	1273	16	0.62	<5	3	116	<5	0.06	<10	<10	38	<10	82	2
8V3671RA/RJ	HL08-62	122183	73.84	75.84	2.00	0.01	0.4	1.68	50	103	<0.5	<5	3.20	2	14	13	19	4.05	<1	0.22	11	0.88	1648	<2	0.02	3	1257	12	0.74	<5	2	127	<5	0.02	<10	<10	31	<10	76	2
8V3671RA/RJ	HL08-62	122184	75.84	76.97	1.13	0.02	1.1	1.41	55	135	<0.5	<5	2.17	2	14	14	26	3.70	<1	0.29	<10	0.59	1141	<2	0.01	3	1210	12	1.04	<5	2	60	<5	<0.01	<10	<10	23	<10	77	2
8V3671RA/RJ	HL08-62	122185	76.97	78.48	1.51	0.04	2.4	1.17	138	172	<0.5	<5	0.71	4	13	21	30	3.76	<1	0.20	<10	0.51	789	4	0.01	3	809	19	1.23	<5	1	31	<5	<0.01	<10	<10	15	<10	115	2
8V3671RA/RJ	HL08-62	122186	78.48	79.48	1.00	0.03	1.8	1.16	175	140	<0.5	<5	1.75	5	13	29	20	3.83	<1	0.22	<10	0.49	970	4	0.01	3	816	15	1.65	<5	2	96	<5	<0.01	<10	<10	14	<10	76	2
8V3671RA/RJ	HL08-62	122187	79.48	80.48	1.00	0.10	1.8	0.78	99	136	<0.5	<5	6.96	3	8	72	14	3.03	<1	0.33	<10	0.30	1747	<2	0.01	3	798	8	2.23	<5	2	252	<5	<0.01	<10	<10	12	<10	64	1
8V3671RA/RJ	HL08-62	122188	80.48	81.81	1.33	0.32	6.3	0.55	177	84	<0.5	<5	2.50	6	11	47	15	4.93	<1	0.28	<10	0.17	766	<2	0.01	3	880	59	4.88	<5	1	106	<5	<0.01	<10	<10	8	18	226	2
8V3671RA/RJ	HL08-62	122189	81.81	82.81	1.00	0.09	2.0	0.81	285	74	<0.5	<5	0.59	8	14	31	14	4.88	<1	0.30	<10	0.29	463	<2	0.01	3	1180	28	4.50	<5	1	24	<5	<0.01	<10	<10	14	<10	97	3
8V3671RA/RJ	HL08-62	122190	82.81	83.81	1.00	0.08	1.6	0.62	255	71	<0.5	<5	3.00	7	13	40	8	4.60	<1	0.33	<10	0.18	895	<2	0.01	3	979	21	>5.00	<5	1	83	<5	<0.01	<10	<10	12	<10	53	3
8V3671RA/RJ	HL08-62	122191	83.81	84.81	1.00	0.35	5.1	0.76	469	109	<0.5	<5	1.28	17	12	29	33	3.29	1	0.26	<10	0.30	798	2	0.01	3	1022	548	2.42	<5	1	44	<5	<0.01	<10	<10	12	<10	619	2
8V3671RA/RJ	HL08-62	122192	84.81	85.81	1.00	0.42	3.2	1.07	160	140	<0.5	<5	1.61	10	13	28	48	3.67	<1	0.33	<10	0.43	1198	2	0.01	3	1090	89	2.32	<5	2	54	<5	<0.01	<10	<10	17	10	590	2
8V3671RA/RJ	HL08-62	122193	85.81	86.81	1.00	0.14	2.2	0.75	249	79	<0.5	<5	0.51	8	14	45	14	4.89	<1	0.28	<10	0.31	497	<2	0.01	3	931	175	4.38	<5	1	27	<5	<0.01	<10	<10	13	<10	147	3
8V3671RA/RJ	HL08-62	122194	86.81	87.69	0.88	0.12	2.9	0.69	481	62	<0.5	<5	0.57	14	14	37	20	4.74	<1	0.37	<10	0.18	266	<2	0.01	3	1193	138	4.82	<5	1	27	<5	<0.01	<10	<10	11	<10	324	3
8V3671RA/RJ	HL08-62	122195	87.69	88.77	1.08	0.19	4.2	0.29	327	71	<0.5	<5	2.41	14	12	57	12	3.91	1	0.19	<10	0.07	745	3	0.01	3	779	207	4.84	<5	1	83	<5	<0.01	<10	<10	6	13	723	2
8V3671RA/RJ	HL08-62	122196	88.77	89.77	1.00	0.10	2.4	1.13	211	57	<0.5	<5	0.84	7	18	43	7	6.42	<1	0.33	<10	0.52	719	<2	0.01	3	1345	63	>5.00	<5	2	37	<5	<0.01	<10	<10	23	<10	144	3
8V3671RA/RJ	HL08-62	122197	89.77	90.77	1.00	0.16	3.5	0.67	563	69	<0.5	<5	1.06	17	17	58	8	4.80	1	0.27	<10	0.29	734	3	0.01	3	1106	262	4.78	<5	1	55	<5	<0.01	<10	<10	14	<10	521	3
8V3671RA/RJ	HL08-62	122198	90.77	91.77	1.00	0.78	56.1	0.73	1212	15	<0.5	<5	0.57	611	13	61	1518	8.80	32	0.19	<10	0.34	594	<2	0.01	3	698	20600	>5.00	33	2	18	<5	<0.01	<10	18	15	914	50300	5
8V3671RA/RJ	HL08-62	122199	90.77	92.64	0.87	0.77	18.5	0.62	1326	48	<0.5	<5	0.42	129	11	63	635	5.10	7	0.18	<10	0.28	452	8	0.01	3	755	2709	>5.00	22	1	19	<5	<0.01	<10	11	155	10100	3	
8V3671RA/RJ	HL08-62	122200	Blank	Blank		<0.01	<0.1	0.07	10	16	<0.5	<5	>15.00	4	1	14	3	0.11	1	0.02	<10	1.87	46	<2	0.01	<1	70	9	0.12	<5	<1	4828	<5	<0.01	<10	<10	1	<10	9	<1
8V3671RA/RJ	HL08-62	122201	Blank	93.90	1.26	0.92	22.1	0.13	340	55	<0.5	<5	1.84	98	4	96	383	4.41	7	0.11	<10	0.03	623	<2	0.01	2	206	7258	>5.00	19	<1	91	<5	<0.01	<10	<10	1	173	10500	3
8V3671RA/RJ	HL08-62	122202	93.90	94.90	1.00	0.18	1.4	0.52	212	54	<0.5	<5	0.79	7	13	38	13	4.76	<1	0.31	<10	0.15	274	<2	0.01	4	365	103	4.97	<5	1	59	<5	<0.01	<10	<10	8	<10	195	3
8V3671RA/RJ	HL08-62	122203	94.90	95.90	1.00	0.18	4.5	0.55	264	91	<0.5	<5	0.45	11	14	67	56	4.40	<1	0.26	<10	0.20	320	14	0.01	5	911	153	4.22	<5	1	24	<5	<0.01	<10	<10	10	<10	454	2
8V3671RA/RJ	HL08-62	122204	95.90	96.79	0.89	0.21	4.0	1.22	366	63	<0.5	<5	0.90	11	19	26	32	5.67	<1	0.39	<10	0.58	910	<2	0.01	5	2129	54	4.18	<5	3	48	<5	<0.01	<10	<10	24	<10	217	3
8V3671RA/RJ	HL08-62	122205	96.79	97.91	1.12	0.05	1.1	0.45	68	113	<0.5	<5	3.84	3	9	114	7	3.94	<1	0.18	<10	0.97	2368	2	0.01	3	937	29	1.79	<5	2	303	<5	<0.01	<10	<10	11	<10	93	2
8V3671RA/RJ	HL08-62	122206	97.91	98.91	1.00	0.07	0.7	0.63	87	378	<0.5	<5	1.81	3	7	142	7	2.66	<1	0.19	<10	0.58	1133	<2	0.01	3	769	12	0.75	<5	2	123	<5	<0.01	<10	<10	12	<10	71	1
8V3671RA/RJ	HL08-62	122207	98.91	100.85	1.94	0.52	4.2	1.09	296	117	<0.5	<5	0.66	9	19	100	23	5.10	<1	0.27	<10	0.54	676	3	0.01	5	1322	95	2.90	<5	3	39	<5	<0.01	<10	<10	21	<10	165	3
8V3671RA/RJ	HL08-62	122208	100.85	101.37	0.52	0.44	16.6	0.29	336	80	<0.5	<5	2.25	27	8	92	178	3.81	<1	0.21	<10	0.07	771	9	0.01	3	321	2367	4.28	9	1	87	<5	<0.01	<10	<10	5	28	1720	2
8V3671RA/RJ	HL08-62	122209	101.37	103.00	1.63	0.12	3.5	0.64	488	147	<0.5	<5	0.60	12	11	91	34	2.97	<1	0.28	<10	0.17	332	4	0.01	4	926	72	2.20	<5	1	33	<5	<0.01	<10	<10	11	<10	104	2
8V3671RA/RJ	HL08-62	122210	103.00	104.00	1.00	0.43	11.0	0.74	260	123	<0.5	<5	0.75	19	13	59	60	3.71	<1	0.29	<10	0.25	433	5	0.01	4	975	1167	3.05	<5	1	39	<5	<0.01	<10	<10	14	23	1647	2
8V3671RA/RJ	HL08-62	122211	104.00	105.27	1.27	0.34	15.9	0.93																																

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Au: 0.5-1.0				Ag: 5-10				Pb/Zn: 2500-5000										5000-10000				>10000													
					1.0-3.0	3.0-5.0	>5.0	5-10	10-50	50-100	>100	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Zr																	
8V3671RA/RJ	HL08-62	122253	156.40	157.74	1.34	0.14	1.6	1.40	526	169	<0.5	<5	2.52	14	15	24	45	4.09	<1	0.34	<10	0.69	1284	<2	0.01	4	1397	50	1.49	<5	2	89	<5	<0.01	<10	<10	32	<10	209	2
8V3671RA/RJ	HL08-62	122254	157.74	159.58	1.84	0.04	8.5	0.81	99	193	<0.5	<5	7.15	4	9	62	23	2.25	<1	0.21	<10	0.41	2221	<2	0.01	3	742	40	0.77	<5	1	593	<5	<0.01	<10	<10	12	<10	176	1
8V3671RA/RJ	HL08-62	122255	159.58	161.60	2.02	0.06	5.5	1.51	189	145	<0.5	<5	1.87	6	20	16	60	4.02	<1	0.37	<10	0.67	1153	<2	0.01	3	1646	35	1.08	<5	2	55	<5	<0.01	<10	<10	35	<10	110	2
8V3671RA/RJ	HL08-62	122256	161.60	162.60	1.00	0.05	3.7	1.20	235	147	<0.5	<5	4.24	7	17	18	42	4.19	<1	0.39	<10	0.50	1463	<2	0.01	3	1420	41	2.53	<5	2	130	<5	<0.01	<10	<10	27	<10	77	2
8V3671RA/RJ	HL08-62	122257	162.60	163.60	1.00	0.06	3.5	1.35	323	112	<0.5	<5	4.51	9	18	19	34	4.49	<1	0.28	<10	0.65	1615	<2	0.01	3	1423	33	2.27	<5	2	136	<5	<0.01	<10	<10	31	<10	123	2
8V3671RA/RJ	HL08-62	122258	163.60	164.60	1.00	0.05	3.4	1.27	268	138	<0.5	<5	4.43	7	16	18	33	3.97	<1	0.37	<10	0.52	1554	<2	0.01	2	1434	24	2.07	<5	2	165	<5	<0.01	<10	<10	30	<10	72	2
8V3671RA/RJ	HL08-62	122259	164.60	166.10	1.50	0.03	3.0	1.27	125	114	<0.5	<5	5.66	4	15	13	33	3.92	<1	0.31	<10	0.57	1801	<2	0.01	2	1472	24	1.79	<5	2	163	<5	<0.01	<10	<10	30	<10	77	2
8V3671RA/RJ	HL08-62	122260	166.10	167.60	1.50	0.02	3.0	1.48	253	131	<0.5	<5	4.35	7	20	12	56	4.18	<1	0.35	<10	0.65	1575	<3	0.01	2	1426	31	1.49	<5	2	132	<5	<0.01	<10	<10	36	<10	100	2
8V3671RA/RJ	HL08-62	122261	167.60	169.47	1.87	0.09	2.1	0.84	470	85	<0.5	<5	3.76	12	13	20	30	3.48	<1	0.25	<10	0.37	1135	<2	0.01	2	1127	22	2.39	<5	1	85	<5	<0.01	<10	<10	22	<10	87	2
8V3671RA/RJ	HL08-62	122262	169.47	171.00	1.53	0.10	3.8	0.63	344	140	<0.5	<5	5.96	13	11	30	42	3.48	<1	0.29	<10	0.23	1526	<2	0.01	2	938	328	3.20	<5	1	198	<5	<0.01	<10	<10	14	<10	637	2
8V3671RA/RJ	HL08-62	122263	171.00	172.89	1.89	0.05	5.2	0.98	262	99	<0.5	<5	7.83	13	14	18	95	4.63	<1	0.25	<10	0.50	2162	<2	0.01	2	1229	621	3.71	<5	2	281	<5	<0.01	<10	<10	24	13	850	2
8V3671RA/RJ	HL08-62	122264	172.89	174.40	1.51	0.02	2.2	1.44	109	117	<0.5	<5	4.21	4	16	15	36	4.72	<1	0.31	<10	0.72	1364	<2	0.01	3	1368	30	2.55	<5	2	134	<5	<0.01	<10	<10	36	<10	89	2
8V3671RA/RJ	HL08-62	122265	174.40	175.90	1.50	0.04	1.7	1.38	143	83	<0.5	<5	7.03	5	14	20	35	4.93	<1	0.29	<10	0.73	1828	<2	0.01	2	1243	29	3.14	<5	2	212	<5	<0.01	<10	<10	32	<10	109	2
8V3671RA/RJ	HL08-62	122266	175.90	177.40	1.50	0.03	1.6	1.35	169	100	<0.5	<5	7.15	5	15	16	34	5.44	<1	0.32	<10	0.66	1866	<2	0.01	2	1249	26	3.73	<5	2	205	<5	<0.01	<10	<10	31	<10	101	3
8V3671RA/RJ	HL08-62	122267	177.40	178.90	1.50	0.01	2.2	1.59	191	92	<0.5	<5	4.52	6	18	19	48	7.13	<1	0.25	<10	0.83	1597	<2	0.01	3	1320	31	>5.00	<5	2	118	<5	<0.01	<10	14	43	<10	91	3
8V3671RA/RJ	HL08-62	122268	178.90	180.20	1.30	0.04	2.0	1.41	466	82	<0.5	<5	2.97	12	16	16	31	7.43	<1	0.30	<10	0.73	1163	<2	0.01	2	1382	25	>5.00	<5	2	85	<5	<0.01	<10	14	31	<10	97	4
8V3671RA/RJ	HL08-62	122269	180.20	181.50	1.30	0.21	2.1	0.67	1033	69	<0.5	<5	5.02	26	12	41	22	4.18	<1	0.23	<10	0.29	1297	<2	0.01	2	800	25	4.09	<5	2	124	<5	<0.01	<10	<10	17	<10	96	2
8V3671RA/RJ	HL08-62	122270	181.50	182.70	1.20	0.13	3.1	0.70	545	70	<0.5	<5	3.39	14	12	31	26	3.30	<1	0.24	<10	0.32	773	<2	0.01	3	742	27	2.53	<5	2	55	<5	<0.01	<10	<10	20	<10	92	2
8V3671RA/RJ	HL08-62	122271	182.70	183.90	1.20	0.42	1.7	0.82	2666	67	<0.5	<5	2.01	64	15	29	30	3.66	<1	0.22	<10	0.43	908	<2	0.01	3	902	18	2.48	<5	1	62	<5	<0.01	<10	<10	19	<10	96	2
8V3671RA/RJ	HL08-62	122272	183.90	185.10	1.20	0.14	0.9	0.97	1173	94	<0.5	<5	4.43	28	15	19	32	3.72	<1	0.30	<10	0.48	1165	<2	0.02	3	1087	14	2.63	<5	2	118	<5	0.02	<10	<10	21	<10	70	2
8V3671RA/RJ	HL08-62	122273	185.10	186.30	1.20	0.11	1.9	1.14	487	82	<0.5	<5	4.21	13	22	25	75	5.19	<1	0.26	<10	0.59	1122	<2	0.02	4	1238	18	3.79	<5	2	108	<5	0.02	<10	<10	30	<10	63	3
8V3671RA/RJ	HL08-62	122274	186.30	187.38	1.08	0.47	2.0	0.95	2573	95	<0.5	<5	4.73	61	17	22	50	3.85	<1	0.35	<10	0.43	1224	<2	0.02	4	1182	30	2.93	<5	3	116	<5	0.01	<10	<10	28	<10	156	2
8V3671RA/RJ	HL08-62	122275	Blank	Blank			<0.01	<0.1	0.07	<5	11	<0.5	9	>15.00	<1	1	9	2	0.06	<1	0.02	1.83	34	<2	0.01	<1	67	<2	0.05	<5	<1	4492	<5	<0.01	<10	<10	2	<10	3	<1
8V3671RA/RJ	HL08-62	122276	187.38	188.90	1.52	0.03	1.3	1.70	108	217	<0.5	<5	4.55	3	19	28	51	4.47	<1	0.36	<10	0.98	1453	<2	0.04	6	1324	25	1.77	<5	4	122	<5	0.02	<10	<10	61	<10	105	3
8V3671RA/RJ	HL08-62	122277	188.90	190.40	1.50	0.05	5.5	1.76	392	93	<0.5	<5	8.52	10	37	14	89	6.95	<1	0.26	<10	1.12	1368	<2	0.02	5	1508	39	4.65	<5	4	543	<5	0.02	<10	12	63	<10	110	3
8V3671RA/RJ	HL08-62	122278	190.40	191.90	1.50	0.12	4.0	1.54	333	93	<0.5	<5	3.17	9	27	28	64	7.25	<1	0.36	<10	0.73	1965	<2	0.02	5	1915	29	>5.00	<5	4	84	<5	0.01	<10	11	62	<10	106	4
8V3671RA/RJ	HL08-62	122279	191.90	193.40	1.50	0.05	3.0	1.68	197	90	<0.5	<5	7.10	6	21	18	53	6.07	<1	0.27	<10	0.90	2233	<2	0.03	3	1686	22	3.52	<5	4	146	<5	<0.01	<10	<10	62	<10	135	3
8V3671RA/RJ	HL08-62	122280	193.40	194.85	1.45	0.17	4.6	1.09	143	90	<0.5	<5	8.56	7	52	26	46	6.16	<1	0.36	<10	0.46	1692	<8	0.02	9	1218	29	>5.00	<5	3	142	<5	<0.01	<10	<10	33	<10	646	3
8V3671RA/RJ	HL08-62	122281	194.85	196.40	1.55	0.01	1.1	1.91	75	94	<0.5	<5	4.45	3	20	17	42	5.34	<1	0.27	<10	1.05	1608	<2	0.02	4	1863	17	1.64	<5	4	129	<5	0.01	<10	<10	70	<10	123	3
8V3671RA/RJ	HL08-62	122282	196.40	197.90	1.50	0.02	1.1	2.16	77	100	<0.5	<5	6.65	3	20	16	53	5.15	<1	0.30	<10	1.17	2067	<2	0.02	4	1570	17	0.99	<5	4	169	<5	0.01	<10	<10	67	<10	141	2</

DILWORTH PROPERTY DRILLING-2008

Certificate Number	DDH	Sample Name	From (m)	To (m)	Inter (m)	Au:				Ag:				Pb/Zn:																										
						0.5-1.0	1.0-3.0	3.0-5.0	>5.0	5-10	10-50	50-100	>100	2500-5000	5000-10000	>10000	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Zr												
8V3672RA/RJ	HL08-63	122446	68.62	70.62	2.00	0.36	0.9	2.19	52	59	<0.5	<5	3.58	3	20	27	24	5.46	<1	0.22	<10	1.25	1593	36	0.03	2	1704	28	0.88	<5	5	103	<5	0.16	<10	<10	67	<10	215	4
8V3672RA/RJ	HL08-63	122447	70.62	72.62	2.00	0.29	5.6	2.13	136	89	<0.5	<5	3.75	6	20	21	214	5.94	<1	0.33	<10	1.20	2820	59	0.02	2	1603	60	1.90	<5	4	58	<5	0.12	<10	66	<10	250	3	
8V3672RA/RJ	HL08-63	122448	72.62	74.62	2.00	0.14	3.8	2.01	103	68	<0.5	<5	4.77	5	20	23	177	5.56	<1	0.23	<10	1.16	3095	18	0.02	2	1588	26	1.60	<5	5	85	<5	0.14	<10	<10	66	<10	244	4
8V3672RA/RJ	HL08-63	122449	74.62	76.62	2.00	0.09	2.3	2.18	58	74	<0.5	<5	3.57	3	19	15	108	5.36	<1	0.28	<10	1.13	1988	25	0.03	2	1687	71	1.05	<5	5	95	<5	0.19	<10	<10	73	<10	232	5
8V3672RA/RJ	HL08-63	122500	Blank	Blank		<0.01	<0.1	0.09	<5	11	<0.5	11	>15.00	<1	1	7	7	0.16	<1	0.03	<10	1.48	100	<2	0.01	<1	106	<2	0.06	<5	<1	5471	<5	<0.01	<10	<10	3	<10	8	<1
8V3672RA/RJ	HL08-63	122501	76.62	78.62	2.00	0.13	2.4	2.26	37	65	<0.5	<5	3.34	3	19	20	163	5.41	<1	0.22	<10	1.10	1768	23	0.04	3	1653	30	0.73	<5	5	136	<5	0.20	<10	<10	71	<10	228	5
8V3672RA/RJ	HL08-63	122502	78.62	80.62	2.00	0.08	3.9	2.24	38	61	<0.5	<5	4.17	3	20	24	239	5.49	<1	0.21	<10	1.22	1857	30	0.03	2	1705	21	0.85	<5	5	197	<5	0.18	<10	<10	73	<10	221	5
8V3672RA/RJ	HL08-63	122503	80.62	82.62	2.00	0.35	5.8	1.99	75	93	<0.5	<5	4.01	4	19	14	247	5.32	<1	0.24	<10	1.03	1914	50	0.02	2	1635	98	1.33	<5	5	122	<5	0.14	<10	<10	67	<10	260	5
8V3672RA/RJ	HL08-63	122504	82.62	84.45	1.83	0.35	4.4	2.50	28	132	<0.5	<5	3.91	3	21	22	284	6.10	<1	0.24	<10	1.42	1766	44	0.02	2	1782	26	0.71	<5	5	124	<5	0.12	<10	<10	70	<10	237	4
8V3672RA/RJ	HL08-63	122505	84.45	86.00	1.55	0.08	4.7	0.97	41	95	<0.5	6	4.42	3	16	10	171	4.82	1	0.49	<10	1.00	2193	42	0.01	2	1506	19	0.97	<5	6	341	<5	<0.01	<10	<10	19	<10	175	2
8V3672RA/RJ	HL08-63	122506	86.00	87.50	1.50	0.13	3.9	1.70	56	86	0.5	5	4.15	4	16	17	167	4.68	1	0.44	<10	1.05	1966	50	0.01	3	1371	42	0.87	<5	4	196	<5	<0.01	<10	<10	32	<10	219	2
8V3672RA/RJ	HL08-63	122507	87.50	88.80	1.30	0.45	3.9	0.97	86	93	<0.5	7	9.58	5	12	10	137	3.80	1	0.34	<10	1.01	2713	49	0.01	2	1064	17	0.67	<5	4	419	<5	<0.01	<10	<10	17	<10	214	2
8V3672RA/RJ	HL08-63	122508	88.80	90.80	2.00	0.12	2.6	2.31	47	115	<0.5	5	4.81	3	21	16	168	5.30	1	0.42	<10	1.26	1874	20	0.01	4	1498	25	0.99	<5	5	207	<5	0.03	<10	<10	73	<10	174	4
8V3672RA/RJ	HL08-63	122509	90.80	92.80	2.00	0.07	2.9	2.24	53	96	<0.5	<5	4.23	3	23	9	134	5.45	1	0.23	<10	1.40	2025	16	0.02	2	1523	33	0.80	<5	6	121	<5	0.10	<10	<10	104	<10	230	4
8V3672RA/RJ	HL08-63	122510	92.80	94.80	2.00	0.04	2.3	2.54	22	149	<0.5	<5	3.91	2	24	36	137	5.41	<1	0.28	19	1.66	1770	12	0.04	9	2026	23	0.42	<5	8	123	<5	0.26	<10	<10	110	<10	184	12
8V3672RA/RJ	HL08-63	122511	94.80	96.65	1.85	0.58	3.9	2.38	29	167	<0.5	<5	3.89	3	22	11	228	5.72	1	0.19	<10	1.54	1772	118	0.03	3	1534	25	0.83	<5	7	106	<5	0.15	<10	<10	123	<10	242	5
8V3672RA/RJ	HL08-63	122512	96.65	97.91	1.26	0.03	0.8	2.40	6	542	<0.5	<5	3.56	1	25	54	44	5.39	<1	0.09	30	1.95	1293	6	0.04	16	2575	18	0.16	<5	6	123	<5	0.19	<10	<10	92	<10	164	10
8V3672RA/RJ	HL08-63	122513	97.91	99.40	1.49	0.17	8.8	1.86	110	104	<0.5	<5	4.44	5	22	17	196	5.11	1	0.22	<10	1.23	3668	24	0.01	3	1415	164	1.83	<5	4	109	<5	0.03	<10	<10	75	<10	287	3
8V3672RA/RJ	HL08-63	122514	99.40	100.90	1.50	0.21	11.4	2.07	64	126	<0.5	6	3.50	4	17	12	196	5.34	<1	0.25	<10	1.46	5431	29	0.01	3	1506	84	1.58	<5	4	98	<5	0.01	<10	12	92	<10	343	2
8V3672RA/RJ	HL08-63	122515	100.90	102.74	1.84	0.09	3.4	2.18	84	76	<0.5	<5	3.79	4	21	16	118	5.60	<1	0.21	<10	1.49	3471	21	0.02	3	1451	36	1.54	<5	6	89	<5	0.11	<10	<10	111	<10	182	4
8V3672RA/RJ	HL08-63	122516	102.74	104.20	1.46	0.14	5.5	2.53	58	96	<0.5	<5	4.60	3	23	8	202	5.95	1	0.27	<10	1.63	2889	46	0.02	2	1484	30	1.00	<5	6	121	<5	0.09	<10	<10	109	<10	222	4
8V3672RA/RJ	HL08-63	122517	104.20	105.70	1.50	0.17	2.9	2.53	55	93	<0.5	5	3.92	3	22	18	167	6.11	1	0.21	<10	1.79	2605	98	0.02	2	1551	61	1.00	<5	6	70	<5	0.05	<10	<10	147	<10	246	3
8V3672RA/RJ	HL08-63	122518	105.70	107.20	1.50	0.15	3.6	2.13	73	74	<0.5	<5	5.21	3	22	7	202	5.22	<1	0.24	<10	1.28	2345	22	0.03	2	1451	30	1.11	<5	6	94	<5	0.08	<10	<10	112	<10	215	4
8V3672RA/RJ	HL08-63	122519	107.20	108.69	1.49	0.20	4.2	1.69	427	81	<0.5	<5	2.84	12	23	19	294	5.11	1	0.15	<10	1.18	2003	11	0.03	3	1570	49	1.72	<5	6	60	<5	0.15	<10	<10	129	<10	165	5
8V3672RA/RJ	HL08-63	122520	108.69	109.77	1.08	0.06	2.7	1.67	39	60	<0.5	<5	3.16	2	22	14	214	4.35	<1	0.13	<10	1.23	1805	6	0.03	3	1456	58	1.17	<5	5	72	<5	0.19	<10	<10	105	<10	121	7
8V3672RA/RJ	HL08-63	122521	127.63	129.10	1.47	0.17	7.5	1.04	140	109	<0.5	<5	4.54	8	15	26	298	4.08	<1	0.22	<10	1.55	2499	25	0.02	3	1212	153	2.57	<5	3	126	<5	0.04	<10	<10	48	11	618	3
8V3672RA/RJ	HL08-63	122522	129.10	130.60	1.50	0.47	5.2	1.42	214	180	<0.5	<5	4.14	9	12	11	287	4.52	<1	0.31	10	0.61	2160	46	0.02	1	1298	105	1.54	<5	3	148	<5	0.02	<10	<10	45	<10	452	2
8V3672RA/RJ	HL08-63	122523	130.60	132.10	1.50	0.14	2.8	1.42	23	80	<0.5	<5	4.98	4	10	21	247	3.83	<1	0.25	<10	1.75	2240	45	0.02	2	1280	70	0.44	<5	3	377	<5	0.01	<10	<10	28	<10	466	2
8V3672RA/RJ	HL08-63	122524	132.10	133.60	1.50	0.31	5.4	1.78	15	118	<0.5	<5	3.30	3	12	12	238	4.74	<1	0.28	13	0.85	1718	27	0.03	1	1223	48	0.52	<5	2	121	<5	0.01	<10	<10	41	<10	301	2
8V3672RA/RJ	HL08-63	122525	Blank	Blank		<0.01	<0.1	0.14	<5	16	<0.5	10	>15.00	<1	1	8	13	0.19	<1	0.05	<10	1.37	123	<2	0.01	<1	1024	<2	0.06	<5	<1	4912	<5	<0.01	<10	<10	3	<10	19	<1
8V3672RA/RJ	HL08-63	122526	133.60	135.10	1.50	0.14	2.6	1.42	44	9																														

Dilworth Surface Chip Samples - 2008

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm		
T08-01 (Yellowstone)												
8V2469RA/RJ	T08-01	139001	435069	6223585	1	0.10	12.7	33	105	115		
8V2469RA/RJ	T08-01	139002	Bearing: 190°		1	0.51	624.0	72	3212	3463		
8V2469RA/RJ	T08-01	139003			1	0.45	14.8	56	3702	6710		
8V2469RA/RJ	T08-01	139004			1	0.20	8.6	8	241	308		
8V2469RA/RJ	T08-01	139005			1	0.11	3.5	<1	63	92		
8V2469RA/RJ	T08-01	139006			1	0.38	143.8	56	328	868		
8V2469RA/RJ	T08-01	139007			1	0.17	9.1	121	359	405		
8V2469RA/RJ	T08-01	139008	435068	6223577	1	0.39	26.9	132	2582	1701		
					8							
T08-02 (Yellowstone)												
8V2690RA/RJ	T08-02	139154	435018	6223616	1	1.03	240.4	32	1576	2672		
8V2690RA/RJ	T08-02	139155	Bearing: 190°		1	0.74	42.4	81	2844	1423		
8V2690RA/RJ	T08-02	139156	435017	6223613	1	0.58	42.0	35	2564	724		
					3							
T08-03 (Yellowstone)												
8V2690RA/RJ	T08-03	139157	435012	6223623	1	0.04	2.6	25	248	112		
8V2690RA/RJ	T08-03	139158	Bearing: 170°		1	0.17	5.7	16	250	127		
8V2690RA/RJ	T08-03	139159			1	1.17	128.0	80	3271	1744		
8V2690RA/RJ	T08-03	139160			1	7.62	475.2	372	12400	12600		
8V2690RA/RJ	T08-03	139161			1	0.95	269.5	90	4556	2692		
8V2690RA/RJ	T08-03	139162	435013	6223617	1	0.74	206.7	67	2206	2096		
					6							
T08-04 (Yellowstone)												
8V2690RA/RJ	T08-04	139163	435040	6223604	1	0.21	6.9	13	112	61		
8V2690RA/RJ	T08-04	139164	Bearing: 50°		1	0.35	5.3	8	128	107		
8V2690RA/RJ	T08-04	139165			1	0.20	12.7	8	252	192		
8V2690RA/RJ	T08-04	139166			1	0.34	6.4	<1	189	205		
8V2690RA/RJ	T08-04	139167			1	0.24	4.3	8	109	134		
8V2690RA/RJ	T08-04	139168			1	0.20	3.0	12	115	134		
8V2690RA/RJ	T08-04	139169			1	0.59	132.0	8	55	77		
8V2690RA/RJ	T08-04	139170			435046	6223609	1	0.10	34.1	22	127	366
					8							
T08-05 (49er)												
8V2469RA/RJ	T08-05	139009	435090	6223471	1	8.82	12.1	149	616	568		
8V2469RA/RJ	T08-05	139010	Bearing: 180°		1	10.31	10.0	192	357	221		
8V2469RA/RJ	T08-05	139011			1	0.14	1.6	57	33	85		
8V2469RA/RJ	T08-05	139012			1	0.14	2.1	81	41	108		
8V2469RA/RJ	T08-05	139013			1	3.51	7.3	113	107	65		
8V2469RA/RJ	T08-05	139014			1	0.10	3.6	125	17	75		
8V2469RA/RJ	T08-05	139015			1	0.12	4.2	87	110	95		
8V2469RA/RJ	T08-05	139016			1	0.12	3.9	86	37	98		
8V2469RA/RJ	T08-05	139017			1	0.19	3.5	57	34	95		
8V2469RA/RJ	T08-05	139018			1	0.79	834.0	71	1585	2699		
8V2469RA/RJ	T08-05	139019			1	0.97	953.0	186	2274	4369		
8V2469RA/RJ	T08-05	139020			1	1.56	14.0	79	183	144		
8V2469RA/RJ	T08-05	139021			1	0.60	17.9	171	72	114		
8V2469RA/RJ	T08-05	139022			1	0.41	17.2	237	364	389		
8V2469RA/RJ	T08-05	139023			435090	6223456	1	0.59	40.5	95	696	698
					15							
T08-06 (Big K)												
8V2596RA/RJ	T08-06	139068	434660	6223929	1	0.11	2.8	154	1077	1996		

Dilworth Surface Chip Samples - 2008

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm	
8V2596RA/RJ	T08-06	139069	434666	6223926	1	0.09	3.4	130	1312	934	
8V2596RA/RJ	T08-06	139070			1	0.20	16.5	997	5188	6437	
8V2596RA/RJ	T08-06	139071			Bearing: 113°	1	0.15	16.5	352	7969	7763
8V2596RA/RJ	T08-06	139072			1	0.67	36.5	2823	9900	12200	
8V2596RA/RJ	T08-06	139073			1	0.05	0.6	15	136	171	
8V2596RA/RJ	T08-06	139074	434666	6223926	1	0.05	0.6	15	164	127	
					7						

T08-07 (Big K)

8V2596RA/RJ	T08-07	139075	434667	6223916	1	0.03	0.5	14	67	471	
8V2596RA/RJ	T08-07	139076	434667	6223916	1	0.08	2.3	77	1244	1838	
8V2596RA/RJ	T08-07	139077			Bearing: 230°	1	0.20	5.2	230	2730	2636
8V2596RA/RJ	T08-07	139078			1	0.04	1.5	41	287	517	
8V2596RA/RJ	T08-07	139079			1	0.05	0.6	39	151	401	
8V2596RA/RJ	T08-07	139080			1	0.06	0.6	32	102	352	
8V2596RA/RJ	T08-07	139081			1	0.06	0.7	23	137	265	
8V2596RA/RJ	T08-07	139082	434661	6223911	1	0.07	0.8	17	45	182	
					8						

T08-08 (Granduc Road)

8V2596RA/RJ	T08-08	139083	434790	6222333	1	0.02	<0.1	9	74	237	
8V2596RA/RJ	T08-08	139084	434790	6222333	1	0.01	0.2	10	118	225	
8V2596RA/RJ	T08-08	139085			Bearing: 200°	1	<0.01	0.3	17	183	417
8V2596RA/RJ	T08-08	139086			1	0.02	0.7	46	755	759	
8V2596RA/RJ	T08-08	139087			1	0.02	0.2	12	71	424	
8V2596RA/RJ	T08-08	139088			1	0.03	0.5	18	195	921	
8V2596RA/RJ	T08-08	139089			1	0.02	0.2	8	120	435	
8V2596RA/RJ	T08-08	139090			1	0.03	0.5	32	319	1555	
8V2596RA/RJ	T08-08	139091			1	0.03	1.5	103	1254	3856	
8V2596RA/RJ	T08-08	139092			1	0.03	7.4	325	6264	8200	
8V2596RA/RJ	T08-08	139093			434786	6222323	1	0.04	7.9	182	7520
					11						

T08-09 (Oxidantal)

8V2596RA/RJ	T08-09	139094	435440	6222816	1	0.08	9.6	15	87	117
8V2596RA/RJ	T08-09	139095	435440	6222816	1	1.36	1736.0	173	5314	10300
8V2596RA/RJ	T08-09	139096			Bearing: 230°	1	0.17	86.7	57	609
8V2596RA/RJ	T08-09	139097	435437	6222813	1	0.06	5.8	21	51	112
					4					

T08-10 (Granduc Road)

8V2596RA/RJ	T08-10	139098	434656	6223478	1	0.01	4.9	32	24	66	
8V2596RA/RJ	T08-10	139099	434656	6223478	1	0.03	9.6	128	442	656	
8V2596RA/RJ	T08-10	139100			Bearing: 123°	1	0.02	0.5	129	37	185
8V2596RA/RJ	T08-10	139101			1	2.23	26.8	897	8186	101000	
8V2596RA/RJ	T08-10	139102			1	0.02	0.5	96	32	209	
8V2596RA/RJ	T08-10	139103			1	1.10	12.2	300	3235	81000	
8V2596RA/RJ	T08-10	139104			1	0.58	58.7	303	26400	4208	
8V2596RA/RJ	T08-10	139105			1	0.42	3.4	186	533	8758	
8V2596RA/RJ	T08-10	139106			1	0.03	0.8	66	187	891	
8V2690RA/RJ	T08-10	139107			1	0.21	2.9	84	455	1790	
8V2690RA/RJ	T08-10	139108			1	0.01	<0.1	99	47	112	
8V2690RA/RJ	T08-10	139109			1	0.01	<0.1	117	64	445	

Dilworth Surface Chip Samples - 2008

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V2690RA/RJ	T08-10	139110			1	<0.01	<0.1	110	45	677
8V2690RA/RJ	T08-10	139111			1	0.01	<0.1	117	35	367
8V2690RA/RJ	T08-10	139112			1	0.03	0.2	90	160	333
8V2690RA/RJ	T08-10	139113			1	0.01	<0.1	86	49	294
8V2690RA/RJ	T08-10	139114			434670	6223469	1	0.01	<0.1	86

17

T08-11 (Snow Show)

8V2508RA/RJ	T08-11	139024	435116	6223348	1	0.15	14.0	219	1814	2194
8V2508RA/RJ	T08-11	139025	Bearing: 203°		1	0.25	27.6	239	3501	3302
8V2508RA/RJ	T08-11	139026			1	0.49	49.4	236	4865	4278
8V2508RA/RJ	T08-11	139027			1	0.18	17.6	312	3313	2734
8V2508RA/RJ	T08-11	139028			1	0.20	15.4	252	2680	2211
8V2508RA/RJ	T08-11	139029			435114	6223342	1	0.27	17.2	331
					6					
8V2508RA/RJ	T08-11	139030	435109	6223345	1	0.23	10.8	129	485	287
8V2508RA/RJ	T08-11	139031	Bearing: 064°		1	0.35	23.6	98	758	277
8V2508RA/RJ	T08-11	139032			1	0.42	40.5	124	626	443
8V2508RA/RJ	T08-11	139033			1	0.46	26.6	167	430	539
8V2508RA/RJ	T08-11	139034			1	0.15	16.5	164	2080	2557
8V2508RA/RJ	T08-11	139035			435114	6223348	1	0.41	115.6	76
					6					

T08-12 (Paulet)

8V2558RA/RJ	T08-12	139036	434939	6223661	1	1.69	10.3	81	1410	1219
8V2558RA/RJ	T08-12	139037	Bearing: 230°		1	1.93	12.3	86	1553	868
8V2558RA/RJ	T08-12	139038			1	1.13	5.2	116	601	2370
8V2558RA/RJ	T08-12	139039			1	0.90	6.5	85	312	516
8V2558RA/RJ	T08-12	139040			1	2.02	14.2	87	1737	1715
8V2558RA/RJ	T08-12	139041			1	2.13	14.6	33	506	232
8V2558RA/RJ	T08-12	139042			1	1.31	15.8	62	599	662
8V2558RA/RJ	T08-12	139043			1	0.71	6.4	92	1122	1308
8V2558RA/RJ	T08-12	139044			1	1.70	40.9	60	1789	522
8V2558RA/RJ	T08-12	139045			1	0.74	5.5	62	454	414
8V2558RA/RJ	T08-12	139046			434931	6223654	1	1.62	3.1	23
					11					

T08-13 (Paulet)

8V2558RA/RJ	T08-13	139047	434862	6223715	1	0.07	1.2	32	84	332
8V2558RA/RJ	T08-13	139048	Bearing: 130°		1	0.28	22.8	651	2950	5530
8V2558RA/RJ	T08-13	139049			1	0.73	12.9	94	2058	2538
8V2558RA/RJ	T08-13	139050	434865	6223712	1	0.15	1.3	60	158	511
					4					

T08-14 (Yellowstone)

8V2558RA/RJ	T08-14	139051	434821	6223607	1	0.09	12.7	237	1477	217
8V2558RA/RJ	T08-14	139052	Bearing: 230°		1	0.32	60.6	791	9192	2600
8V2558RA/RJ	T08-14	139053			1	0.28	20.3	319	3944	3163
8V2558RA/RJ	T08-14	139054			1	0.14	11.1	49	1338	381
8V2558RA/RJ	T08-14	139055			1	0.43	9.5	62	912	401
8V2558RA/RJ	T08-14	139056			1	0.18	8.1	50	633	273

Dilworth Surface Chip Samples - 2008

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V2558RA/RJ	T08-14	139057			1	0.20	8.9	78	500	313
8V2558RA/RJ	T08-14	139058	434815	6223602	1	0.23	6.4	67	247	164
					8					

T08-15 (Paulet)

8V2558RA/RJ	T08-15	139059	434749	6223724	1	0.10	1.5	86	103	375
8V2558RA/RJ	T08-15	139060	Bearing: 230°		1	1.33	56.5	929	27100	9500
8V2558RA/RJ	T08-15	139061			1	0.36	25.9	516	14200	15200
8V2558RA/RJ	T08-15	139062			1	0.24	18.7	360	10700	10000
8V2558RA/RJ	T08-15	139063	434745	6223721	1	0.20	9.2	169	3988	3917
					5					

T08-16 (Paulet)

8V2596RA/RJ	T08-16	139065	434766	6223709	1	0.41	23.7	784	9900	7169
8V2596RA/RJ	T08-16	139066	Bearing: 210°		1	0.36	12.8	263	6453	1708
8V2596RA/RJ	T08-16	139067	434765	6223706	1	0.28	5.8	95	2722	965
					3					

T08-17 (49er)

8V2690RA/RJ	T08-17	139115	435130	6223247	1	0.39	8.7	266	842	831
8V2690RA/RJ	T08-17	139116	Bearing: 123°		1	0.51	11.1	402	1265	1585
8V2690RA/RJ	T08-17	139117			1	0.41	13.4	295	2203	2447
8V2690RA/RJ	T08-17	139118			1	0.42	9.4	252	1102	728
8V2690RA/RJ	T08-17	139119			1	0.28	4.4	217	232	619
8V2690RA/RJ	T08-17	139120	435135	6223244	1	0.29	5.4	80	303	497
					6					

T08-18 (49er)

8V2690RA/RJ	T08-18	139121	435210	6223245	1	0.66	16.5	284	1536	710
8V2690RA/RJ	T08-18	139122	Bearing: 220°		1	2.15	40.2	247	2974	1177
8V2690RA/RJ	T08-18	139123			1	0.74	51.0	511	9333	3099
8V2690RA/RJ	T08-18	139124			1	3.09	96.9	838	13600	7016
8V2690RA/RJ	T08-18	139125			1	2.51	45.0	545	6946	6849
8V2690RA/RJ	T08-18	139126	435206	6223240	1	5.99	115.0	404	10400	836
					6					

T08-19 (Below Helen)

8V2690RA/RJ	T08-19	139127	435320	6222816	1	0.18	2.6	18	144	119
8V2690RA/RJ	T08-19	139128	Bearing 156°		1	0.18	4.8	40	151	94
8V2690RA/RJ	T08-19	139129			1	0.29	5.5	57	150	143
8V2690RA/RJ	T08-19	139130			1	0.17	4.4	35	79	89
8V2690RA/RJ	T08-19	139131			1	0.13	4.2	37	67	75
8V2690RA/RJ	T08-19	139132			1	0.04	1.9	14	30	36
8V2690RA/RJ	T08-19	139133			1	0.13	7.1	30	33	34
8V2690RA/RJ	T08-19	139134			1	0.04	2.0	25	45	39
8V2690RA/RJ	T08-19	139135			1	0.08	3.0	22	29	21
8V2690RA/RJ	T08-19	139136			1	0.04	2.1	14	16	18
8V2690RA/RJ	T08-19	139137			1	0.24	2.9	12	14	11
8V2690RA/RJ	T08-19	139138			1	0.12	3.1	9	62	33
8V2690RA/RJ	T08-19	139139			435325	6222804	1	0.27	3.6	15
					13					

T08-20 (Granduc Road)

8V2690RA/RJ	T08-20	139140	434838	6222421	1	0.02	10.7	210	272	111
8V2690RA/RJ	T08-20	139141	Bearing 200°		1	0.01	0.5	99	19	97
8V2690RA/RJ	T08-20	139142			1	0.02	0.8	76	25	81
8V2690RA/RJ	T08-20	139143			1	<0.01	1.3	85	74	126

Dilworth Surface Chip Samples - 2008

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V2690RA/RJ	T08-20	139144	Bearing: 209°		1	0.02	0.7	82	30	104
8V2690RA/RJ	T08-20	139145	Bearing: 209°		1	0.02	0.8	99	155	150
8V2690RA/RJ	T08-20	139146	Bearing: 209°		1	0.02	0.2	96	27	92
8V2690RA/RJ	T08-20	139147	434835	6222413	1	<0.01	0.2	85	23	77

8

T08-21 (49er)

8V2690RA/RJ	T08-21	139148	435145	6223440	1	0.25	4.5	58	97	116
8V2690RA/RJ	T08-21	139149	Bearing: 209°		1	0.38	4.0	30	307	452
8V2690RA/RJ	T08-21	139150	Bearing: 209°		1	0.28	3.5	46	267	196
8V2690RA/RJ	T08-21	139151	Bearing: 209°		1	0.56	9.2	46	891	754
8V2690RA/RJ	T08-21	139152	Bearing: 209°		1	0.23	3.9	44	315	327
8V2690RA/RJ	T08-21	139153	435142	6223435	1	0.20	2.0	42	80	96

6

T08-22 (Oxidantal)

8V2698RA/RJ	T08-22	139171	435263	6222737	1	0.06	3.8	19	79	72
8V2698RA/RJ	T08-22	139172	Bearing: 180°		1	0.25	19.7	44	1680	2037
8V2698RA/RJ	T08-22	139173	435263	6222734	1	0.21	9.6	12	481	637

3

T08-23 (Granduc North)

8V2698RA/RJ	T08-23	139174	434706	6225150	1	1.29	36.1	11	919	309
8V2698RA/RJ	T08-23	139175	Bearing: 210°		1	0.07	5.0	7	1026	586
8V2698RA/RJ	T08-23	139176	Bearing: 210°		1	0.39	9.1	10	556	786
8V2698RA/RJ	T08-23	139177	434704	6225147	1	2.81	127.0	12	1267	173

4

T08-24 (Granduc North)

8V2698RA/RJ	T08-24	139178	434678	6225129	1	0.05	0.9	21	189	158
8V2698RA/RJ	T08-24	139179	Bearing: 210°		1	0.05	2.9	16	859	857
8V2698RA/RJ	T08-24	139180	Bearing: 210°		1	0.07	1.5	18	206	320
8V2698RA/RJ	T08-24	139181	Bearing: 210°		1	0.07	2.3	8	513	492
8V2698RA/RJ	T08-24	139182	Bearing: 210°		1	0.04	1.7	24	533	505
8V2698RA/RJ	T08-24	139183	Bearing: 210°		1	0.06	1.3	13	531	1036
8V2698RA/RJ	T08-24	139184	Bearing: 210°		1	0.05	8.1	18	159	112
8V2698RA/RJ	T08-24	139185	434674	6225122	1	0.02	0.9	2	63	76

8

T08-25 (Granduc North)

8V2698RA/RJ	T08-25	139186	434675	6225122	1	0.34	1.6	12	115	368
8V2698RA/RJ	T08-25	139187	Bearing: 210°		1	0.18	2.3	14	579	1131
8V2698RA/RJ	T08-25	139188	Bearing: 210°		1	0.17	4.1	55	885	228
8V2698RA/RJ	T08-25	139189	434673	6225119	1	0.19	1.3	71	59	129

4

T08-26 (Tangerine)

8V2698RA/RJ	T08-26	139190	434665	6224828	1	0.31	1.3	59	22100	141
8V2698RA/RJ	T08-26	139191	Bearing: 330°		1	0.87	65.3	315	7666	436
8V2698RA/RJ	T08-26	139192	Bearing: 330°		1	1.7	193.0	101	21400	1064
8V2698RA/RJ	T08-26	139193	Bearing: 330°		1	1.82	141.0	120	30500	198
8V2698RA/RJ	T08-26	139194	Bearing: 330°		1	0.57	175.0	176	94000	724
8V2698RA/RJ	T08-26	139195	Bearing: 330°		1	0.64	232.7	118	114000	1794
8V2698RA/RJ	T08-26	139196	Bearing: 330°		1	0.91	260.4	158	62000	1241
8V2698RA/RJ	T08-26	139197	Bearing: 330°		1	1.29	207.7	646	39000	4280
8V2698RA/RJ	T08-26	139198	Bearing: 330°		1	4.46	347.5	365	115000	5933
8V2698RA/RJ	T08-26	139199	Bearing: 330°		1	1.17	319.6	143	26000	432

Dilworth Surface Chip Samples - 2008

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V2698RA/RJ	T08-26	139200			1	0.28	237.3	105	3407	841
8V2698RA/RJ	T08-26	139201			1	0.16	53.2	55	1412	210
8V2698RA/RJ	T08-26	139202	434659	6224839	1	0.5	17.8	68	1412	228

13

T08-27 (Tangerine)

8V2698RA/RJ	T08-27	139203	434673	6224784	1	0.12	3.9	16	131	85
8V2698RA/RJ	T08-27	139204			1	0.06	3.4	14	75	111
8V2698RA/RJ	T08-27	139205	Bearing: 260°		1	0.32	5.3	10	81	69
8V2698RA/RJ	T08-27	139206			1	0.10	1.9	8	93	163
8V2698RA/RJ	T08-27	139207	434668	6224783	1	0.08	1.1	9	73	65

5

T08-28 (Tangerine)

8V2698RA/RJ	T08-28	139208	434668	6224776	1	0.02	3.7	7	419	109
8V2698RA/RJ	T08-28	139209	Bearing: 260°		1	0.15	2.9	26	212	179
8V2698RA/RJ	T08-28	139210	434665	6224775	1	0.67	4.8	9	476	80

3

T08-29 (Tangerine)

8V2698RA/RJ	T08-29	139211	434676	6224770	1	0.18	1.9	3	133	15
8V2698RA/RJ	T08-29	139212	Bearing: 260°		1	0.29	19.7	15	1031	521
8V2698RA/RJ	T08-29	139213	434673	6224769	1	0.07	1.0	11	31	38

3

T08-30 (Tangerine)

8V2698RA/RJ	T08-30	139214	434705	6224762	1	0.06	<0.1	28	24	89
8V2698RA/RJ	T08-30	139215	Bearing: 190°		1	0.03	<0.1	25	17	94
8V2698RA/RJ	T08-30	139216			1	0.09	<0.1	20	18	42
8V2698RA/RJ	T08-30	139217	434704	6224758	1	<0.01	0.2	31	18	36

4

T08-31 (Granduc Road)

8V2768RA/RJ	T08-31	139218	434637	6223543	1	0.05	5.2	80	276	344
8V2768RA/RJ	T08-31	139219			1	0.02	1.8	159	56	366
8V2768RA/RJ	T08-31	139220			1	0.40	2.4	114	95	1021
8V2768RA/RJ	T08-31	139221			1	0.30	2.6	106	269	2292
8V2768RA/RJ	T08-32	139222			1	0.05	0.7	56	61	373
8V2768RA/RJ	T08-31	139223			1	1.51	3.4	165	274	2140
8V2768RA/RJ	T08-31	139224	Bearing: 190°		1	0.23	2.1	56	199	1004
8V2768RA/RJ	T08-31	139225			1	0.14	2.0	52	215	2258
8V2768RA/RJ	T08-31	139226			1	0.16	1.4	93	103	353
8V2768RA/RJ	T08-31	139227			1	0.19	1.8	132	63	200
8V2768RA/RJ	T08-31	139228			1	0.16	1.8	138	105	423
8V2768RA/RJ	T08-31	139229			1	0.08	0.5	50	36	131
8V2768RA/RJ	T08-31	139230	434635	6223530	1	0.64	3.6	147	130	649

13

T08-32 (Granduc Road)

8V2768RA/RJ	T08-32	139231	434700	6223326	1	0.16	2.4	138	263	234
8V2768RA/RJ	T08-32	139232			1	0.06	<0.1	89	52	204
8V2768RA/RJ	T08-32	139233			1	0.04	<0.1	77	53	121
8V2768RA/RJ	T08-32	139234			1	0.03	<0.1	77	54	171
8V2768RA/RJ	T08-32	139235			1	0.02	<0.1	153	58	591
8V2768RA/RJ	T08-32	139236			1	0.04	<0.1	139	97	737
8V2768RA/RJ	T08-32	139237			1	0.07	<0.1	152	131	780
8V2768RA/RJ	T08-32	139238	Bearing: 129°		1	0.04	<0.1	80	27	494

Dilworth Surface Chip Samples - 2008

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V2768RA/RJ	T08-32	139239			1	0.04	<0.1	93	34	225
8V2768RA/RJ	T08-32	139240			1	0.02	0.2	56	266	286
8V2768RA/RJ	T08-32	139241			1	0.46	0.9	218	174	449
8V2768RA/RJ	T08-32	139242			1	0.12	4.9	367	3287	2036
8V2768RA/RJ	T08-32	139243			1	0.03	<0.1	96	372	748
8V2768RA/RJ	T08-32	139244			1	0.06	0.3	103	155	357
8V2768RA/RJ	T08-32	139245	434712	6223317	1	0.01	<0.1	124	45	292

15

T08-33 (Granduc Road)

8V2768RA/RJ	T08-33	139246	434830	6222994	1	<0.01	<0.1	72	19	145
8V2768RA/RJ	T08-33	139247			1	<0.01	<0.1	100	12	106
8V2768RA/RJ	T08-33	139248			1	<0.01	<0.1	104	8	95
8V2768RA/RJ	T08-33	139249			1	0.01	<0.1	81	9	93
8V2768RA/RJ	T08-33	139250			1	<0.01	0.3	76	9	57
8V2768RA/RJ	T08-33	139251			1	0.02	0.5	81	18	86
8V2768RA/RJ	T08-33	139252			1	0.02	0.6	72	16	99
8V2768RA/RJ	T08-33	139253			1	0.01	1.7	95	82	72
8V2768RA/RJ	T08-33	139254			1	<0.01	1.6	66	19	81
8V2768RA/RJ	T08-33	139255	434833	6222984	1	<0.01	0.4	72	7	48

10

T08-34 (Granduc Road)

8V3283RA/RJ	T08-34	139256	434826	6222405	1	0.01	0.5	34	10	81
8V3283RA/RJ	T08-34	139257			1	<0.01	0.3	62	23	128
8V3283RA/RJ	T08-34	139258			1	<0.01	0.1	48	16	99
8V3283RA/RJ	T08-34	139259			1	0.02	0.5	85	24	115
8V3283RA/RJ	T08-34	139260			1	0.02	0.6	81	24	191
8V3283RA/RJ	T08-34	139261			1	0.05	2.1	128	900	731
8V3283RA/RJ	T08-34	139262			1	0.06	3.0	107	613	2965
8V3283RA/RJ	T08-34	139263			1	0.05	1.9	94	122	548
8V3283RA/RJ	T08-34	139264			1	0.02	2.4	79	1116	927
8V3283RA/RJ	T08-34	139265			1	0.02	1.3	106	136	447
8V3283RA/RJ	T08-34	139266			1	0.01	1.6	107	517	841
8V3283RA/RJ	T08-34	139267			1	0.02	2.5	96	302	448

12

T08-35 (Chicago South)

8V2768RA/RJ	T08-35	139268	435123	6224065	1	0.71	35.9	40	356	670
8V2768RA/RJ	T08-35	139269			1	0.80	47.0	42	341	1034
8V2768RA/RJ	T08-35	139270			1	0.88	57.2	47	311	641
8V2768RA/RJ	T08-35	139271	435119	6224064	1	0.52	25.1	29	325	397

4

T08-36 (Chicago South)

8V2768RA/RJ	T08-36	139272	435067	6224046	1	0.64	8.8	30	166	218
8V2768RA/RJ	T08-36	139273			1	5.27	712.5	141	4647	7557
8V2768RA/RJ	T08-36	139274			1	0.97	49.7	104	555	2413
8V2768RA/RJ	T08-36	139275			1	0.59	24.0	76	282	1173
8V2768RA/RJ	T08-36	139276			1	0.76	11.5	69	244	736
8V2768RA/RJ	T08-36	139277			1	0.77	40.0	49	242	267
8V2768RA/RJ	T08-36	139278	435060	6224046	1	1.53	18.7	11	190	202

7

T08-37 (Chicago South)

Dilworth Surface Chip Samples - 2008

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V2768RA/RJ	T08-37	139279	435076	6224052	1	0.12	7.0	52	111	420
8V2768RA/RJ	T08-37	139280	Bearing 270		1	0.38	37.8	45	99	244
			435074	6224052						
					2					

T08-38 (Chicago South)										
8V2821RA/RJ	T08-38	139281	435177	6224064	1	8.21	126.0	293	11600	11800
8V2821RA/RJ	T08-38	139282	Bearing 340		1	6.24	101.0	904	11500	23200
8V2821RA/RJ	T08-38	139283			1	7.96	127.0	1250	9496	22900
8V2821RA/RJ	T08-38	139284			1	11.30	126.0	1836	12500	36600
8V2821RA/RJ	T08-38	139285			1	2.67	168.0	133	1541	2513
8V2821RA/RJ	T08-38	139286	435175	6224070	1	4.34	176.0	64	1194	2747
					6					

T08-39 (Chicago South)										
8V2821RA/RJ	T08-39	139287	435060	6224040	1	0.56	47.9	12	189	157
8V2821RA/RJ	T08-39	139288	Bearing 270		1	0.19	12.2	13	66	113
8V2821RA/RJ	T08-39	139289			1	1.73	271.9	42	1536	1670
8V2821RA/RJ	T08-39	139290			1	4.52	659.1	60	3495	3346
8V2821RA/RJ	T08-39	139291	435055	6224040	1	0.89	23.0	32	1085	942
					5					

T08-40 (Hammer)										
8V2821RA/RJ	T08-40	139292	435099	6223778	1	4.13	213.3	162	2025	5000
8V2821RA/RJ	T08-40	139293	Bearing 130		1	4.26	243.7	87	2634	4010
8V2821RA/RJ	T08-40	139294			1	2.53	239.4	91	1693	2112
8V2821RA/RJ	T08-40	139295	435102	6223775	1	22.46	1281.0	476	3834	6338
					4					

T08-41 (Hammer)										
8V2821RA/RJ	T08-41	139296	435098	6223769	1	7.14	319.2	42	2747	649
8V2821RA/RJ	T08-41	139297	Bearing 134		1	4.52	318.5	29	1725	291
8V2821RA/RJ	T08-41	139298			1	3.77	152.0	49	1020	882
8V2821RA/RJ	T08-41	139299	435101	6223766	1	3.20	158.0	19	1367	161
					4					

T08-42 (Paulet)										
8V2821RA/RJ	T08-42	139300	434767	6223821	1	0.52	9.6	200	2284	15400
8V2821RA/RJ	T08-42	139301	Bearing 139		1	0.45	9.7	157	1349	3184
8V2821RA/RJ	T08-42	139302			1	0.74	9.4	175	2338	2057
8V2821RA/RJ	T08-42	139303			1	0.37	3.6	135	896	5242
8V2821RA/RJ	T08-42	139304			1	0.24	7.2	146	2896	5134
8V2821RA/RJ	T08-42	139305	434771	6223816	1	0.21	6.2	177	2843	3855
					6					

T08-43 (Paulet)										
8V2821RA/RJ	T08-43	139306	434726	6223766	1	0.08	2.8	73	625	377
8V2821RA/RJ	T08-43	139307	Bearing 145		1	0.07	2.7	119	776	474
8V2821RA/RJ	T08-43	139308			1	0.05	1.1	58	694	612
8V2821RA/RJ	T08-43	139309			1	0.16	7.6	172	3561	711
	T08-43	139310			434729	6223762	1	0.25	10.2	80
					5					

Dilworth Surface Chip Samples - 2008

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
T08-44 (Chicago South)										
8V2821RA/RJ	T08-44	139311	435168	6224170	1	0.22	16.0	19	942	1590
8V2821RA/RJ	T08-44	139312	Bearing 220		1	0.30	47.3	5	141	162
8V2821RA/RJ	T08-44	139313			1	0.31	15.9	8	90	82
8V2821RA/RJ	T08-44	139314			1	0.68	98.4	11	417	1865
8V2821RA/RJ	T08-44	139315			1	1.51	75.2	27	538	1396
8V2821RA/RJ	T08-44	139316			1	0.64	203.8	38	429	903
8V2821RA/RJ	T08-44	139317			1	20.73	198.0	27	805	2035
8V2821RA/RJ	T08-44	139318			1	0.39	25.1	15	105	180
8V2821RA/RJ	T08-44	139319			1	0.32	21.9	13	94	105
8V2821RA/RJ	T08-44	139320			1	0.44	38.6	19	173	239
8V2821RA/RJ	T08-44	139321			1	0.94	123.0	19	208	227
8V2821RA/RJ	T08-44	139322	1	1.04	49.8	20	125	118		
8V2821RA/RJ	T08-44	139323	435160	6224160	1	0.70	29.7	27	125	366

13

T08-45 (Chicago South)										
8V2820RA/RJ	T08-45	139324	435090	6224080	1	0.10	10.2	10	126	156
8V2820RA/RJ	T08-45	139325	Bearing 220		1	3.53	155.0	45	2169	1415
8V2820RA/RJ	T08-45	139326			1	0.03	3.7	16	34	48
8V2820RA/RJ	T08-45	139327	435087	6224077	1	0.40	6.1	24	85	127

4

T08-46 (Chicago South)										
8V2820RA/RJ	T08-46	139328	435089	6224054	1	0.37	12.7	20	95	217
8V2820RA/RJ	T08-46	139329	Bearing 220		1	0.43	14.5	15	131	133
8V2820RA/RJ	T08-46	139330			1	0.63	22.8	43	196	671
8V2820RA/RJ	T08-46	139331	435086	6224051	1	0.58	27.5	32	152	324

4

T08-47 (Hammer)										
8V2820RA/RJ	T08-47	139332	434888	6223870	1	1.32	9.2	106	1854	2153
8V2820RA/RJ	T08-47	139333	Bearing 136		1	11.82	42.4	45	2290	1271
8V2820RA/RJ	T08-47	139334	434890	6223868	1	11.15	78.2	85	9961	1577

3

T08-48 (Hammer)										
8V2820RA/RJ	T08-48	139335	434904	6223825	1	2.04	12.2	367	1699	9374
8V2820RA/RJ	T08-48	139336	Bearing 134		1	1.59	39.1	1487	5088	25500
8V2820RA/RJ	T08-48	139337	434906	6223823	1	1.56	55.5	853	4880	14700

3

T08-49 (Paulet)										
8V2820RA/RJ	T08-49	139338	434825	6223705	1	0.58	28.8	395	18600	722
8V2820RA/RJ	T08-49	139339	Bearing 160		1	0.99	17.7	143	7593	6145
8V2820RA/RJ	T08-49	139340			1	0.78	13.9	165	2448	7140
8V2820RA/RJ	T08-49	139341	434826	6223701	1	1.21	66.7	3643	49400	49800

4

Dilworth Surface Chip Samples - 2008

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
T08-50 (Bee)										
8V2892RA/RJ	T08-50	139342	435318	6222553	1	0.19	1.7	6	24	63
8V2892RA/RJ	T08-50	139343	Bearing 118	6222553	1	0.04	2.0	4	42	48
8V2892RA/RJ	T08-50	139344			1	0.01	0.9	5	20	43
8V2892RA/RJ	T08-50	139345			1	0.06	1.8	4	24	27
8V2892RA/RJ	T08-50	139346			1	0.09	3.9	9	50	154
8V2892RA/RJ	T08-50	139347			1	0.28	6.0	6	34	20
8V2892RA/RJ	T08-50	139348			1	0.24	5.9	3	36	29
8V2892RA/RJ	T08-50	139349			1	0.06	1.5	7	17	41
8V2892RA/RJ	T08-50	139350			1	0.17	3.6	15	39	78
8V2892RA/RJ	T08-50	139351	435327	6222548	1	0.22	3.2	17	68	158

10

T08-51(Bee)										
8V2892RA/RJ	T08-51	139352	435318	6222545	1	0.15	3.5	7	42	39
8V2892RA/RJ	T08-51	139353	Bearing: 118°	6222545	1	0.14	3.7	5	71	61
8V2892RA/RJ	T08-51	139354			1	0.33	16.1	20	241	397
8V2892RA/RJ	T08-51	139355	435322	6222543	1	1.37	348.8	39	1386	389

4

T08-52 (Sparky)										
8V2892RA/RJ	T08-52	139356	435283	6222509	1	4.47	750.3	198	2069	2224
8V2892RA/RJ	T08-52	139357	Bearing: 180°	6222509	1	1.91	1436.0	860	11800	23400
8V2892RA/RJ	T08-52	139358			1	0.13	10.8	45	158	404
8V2892RA/RJ	T08-52	139359	435283	6222505	1	1.18	554.2	272	3507	5839

4

T08-53 (Bee)										
8V2892RA/RJ	T08-53	139360	435294	6222554	1	1.91	105.0	129	1532	2881
8V2892RA/RJ	T08-53	139361	Bearing:165°	6222554	1	0.50	17.5	62	685	2184
8V2892RA/RJ	T08-53	139362			1	1.26	480.8	153	3003	4220
8V2892RA/RJ	T08-53	139363			1	1.43	144.0	72	3043	1557
8V2892RA/RJ	T08-53	139364			1	1.61	110.0	184	4757	3623
8V2892RA/RJ	T08-53	139365			1	0.81	319.0	72	555	719
8V2892RA/RJ	T08-53	139366			1	0.52	665.4	42	659	409
8V2892RA/RJ	T08-53	139367			1	1.23	397.2	59	689	1132
8V2892RA/RJ	T08-53	139368			1	0.30	7.1	17	52	64
8V2892RA/RJ	T08-53	139369			1	0.30	6.6	21	59	56
8V2892RA/RJ	T08-53	139370			1	0.28	22.9	17	237	80
8V2892RA/RJ	T08-53	139371			1	0.22	6.8	17	60	35
8V2892RA/RJ	T08-53	139372			435297	6222541	1	0.66	9.4	30

13

T08-54 (Bee)										
8V2892RA/RJ	T08-54	139373	435283	6222556	1	0.91	499.7	41	1995	160
8V2892RA/RJ	T08-54	139374	Bearing: 185°	6222556	1	0.97	145.0	81	798	855
8V2892RA/RJ	T08-54	139375			1	0.93	231.9	119	1068	565
8V2892RA/RJ	T08-54	139376			1	1.42	884.1	148	2333	2653
8V2892RA/RJ	T08-54	139377			1	0.75	97.2	45	935	218
8V2892RA/RJ	T08-54	139378			1	0.15	16.8	17	152	199
8V2892RA/RJ	T08-54	139379			435282	6222549	1	0.28	21.1	17

7

Dilworth Surface Chip Samples - 2008

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
T08-55 (Sparky)										
8V2936RA/RJ	T08-55	139380	435299	6222496	1	0.38	6.6	26	79	68
8V2936RA/RJ	T08-55	139381	Bearing:190°		1	0.59	102.0	55	141	73
8V2936RA/RJ	T08-55	139382			1	0.32	2.8	39	28	74
8V2936RA/RJ	T08-55	139383			1	0.62	8.8	54	154	273
8V2936RA/RJ	T08-55	139384			435298	6222491	1	0.83	31.7	74

5

T08-56 (Sparky)										
8V2936RA/RJ	T08-56	139385	435333	6222455	1	0.74	48.7	8	51	25
8V2936RA/RJ	T08-56	139386	Bearing: 118°		1	1.05	10.9	9	63	67
8V2936RA/RJ	T08-56	139387			1	0.42	24.6	12	120	32
8V2936RA/RJ	T08-56	139388			1	5.21	23.8	11	81	38
8V2936RA/RJ	T08-56	139389			1	0.26	156.3	22	294	462
8V2936RA/RJ	T08-56	139390	435338	6222452	1	0.31	45.4	25	67	35

6

T08-57 (Sparky)										
8V2936RA/RJ	T08-57	139391	435363	6222435	1	0.11	2.7	22	61	151
8V2936RA/RJ	T08-57	139392	Bearing: 360°		1	0.21	3.3	13	63	82
8V2936RA/RJ	T08-57	139393			1	0.19	9.3	12	108	105
8V2936RA/RJ	T08-57	139394			1	0.12	8.0	17	79	144
8V2936RA/RJ	T08-57	139395			435363	6222440	1	0.22	2.8	6

5

T08-58 (Sparky)										
8V2936RA/RJ	T08-58	139396	435285	6222505	1	0.56	36.8	61	963	477
8V2936RA/RJ	T08-58	139397	Bearing: 190°		1	0.26	8.7	41	162	209
			435285	6222503						

2

T08-59 (Sparky)										
8V3008RA/RJ	T08-59	139398	435299	6222524	1	0.41	4.6	2	64	24
8V3008RA/RJ	T08-59	139399	Bearing: 148°		1	0.54	284.7	3	918	87
8V3008RA/RJ	T08-59	139400			1	0.62	193.0	36	1173	1213
8V3008RA/RJ	T08-59	139401			1	0.25	10.6	2	60	39
8V3008RA/RJ	T08-59	139402			1	0.30	5.7	6	41	38
8V3008RA/RJ	T08-59	139403			1	0.29	8.6	12	32	21
8V3008RA/RJ	T08-59	139404			1	0.50	6.7	2	37	18
8V3008RA/RJ	T08-59	139405			1	0.33	9.1	5	61	51
8V3008RA/RJ	T08-59	139406			1	0.32	21.2	9	279	83
8V3008RA/RJ	T08-59	139407			1	1.46	24.0	19	418	131
8V3008RA/RJ	T08-59	139408			1	0.25	4.3	1	107	14
8V3008RA/RJ	T08-59	139409			1	0.15	8.2	<1	356	22
8V3008RA/RJ	T08-59	139410			1	0.27	12.3	<1	887	11
8V3008RA/RJ	T08-59	139411			1	0.23	23.8	9	469	102
8V3008RA/RJ	T08-59	139412			1	0.20	7.5	12	259	142
8V3008RA/RJ	T08-59	139413			1	0.25	7.7	24	274	276
8V3008RA/RJ	T08-59	139414			1	0.21	5.3	17	279	120
8V3008RA/RJ	T08-59	139415			435309	6222509	1	0.34	5.6	22

18

Dilworth Surface Chip Samples - 2008

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
T08-60 (Big K)										
8V3008RA/RJ	T08-60	139416	434650	6224110	1	0.12	8.2	147	4781	6252
8V3008RA/RJ	T08-60	139417	Bearing: 240°		1	0.12	6.9	54	4208	4666
8V3008RA/RJ	T08-60	139418			1	0.13	16.2	121	10600	15100
8V3008RA/RJ	T08-60	139419			1	0.12	8.5	82	5320	4943
8V3008RA/RJ	T08-60	139420			1	0.11	8.7	77	4953	4225
8V3008RA/RJ	T08-60	139421			1	0.11	12.0	236	6327	7980
8V3008RA/RJ	T08-60	139422			1	0.17	10.0	63	5954	7259
8V3008RA/RJ	T08-60	139423			1	0.21	17.6	220	6901	6737
8V3008RA/RJ	T08-60	139424	434642	6224106	1	0.05	6.5	80	3182	4423

9

T08-61 (Big K)										
8V3008RA/RJ	T08-61	139425	434603	6223946	1	0.13	18.3	317	6325	4172
8V3008RA/RJ	T08-61	139426	Bearing: 140°		1	0.33	36.1	1081	15400	9135
8V3008RA/RJ	T08-61	139427			1	0.47	25.6	884	8355	9600
8V3008RA/RJ	T08-61	139428	434606	6223943	1	0.08	4.2	102	991	1136

4

T08-62 (Big K)										
8V3008RA/RJ	T08-62	139429	434645	6223965	1	0.06	2.9	68	696	401
8V3008RA/RJ	T08-62	139430	Bearing: 165°		1	0.11	21.4	283	10100	3505
8V3008RA/RJ	T08-62	139431			1	0.24	2.9	61	1341	895
8V3008RA/RJ	T08-62	139432			1	0.17	10.9	172	4720	4073
8V3008RA/RJ	T08-62	139433			1	0.33	38.0	196	13800	758
8V3008RA/RJ	T08-62	139434	434647	6223959	1	0.13	7.9	59	2714	1637

6

T08-63 (Anaconda)										
8V3008RA/RJ	T08-63	139451	435090	6222252	1	0.04	1.9	58	109	166
8V3008RA/RJ	T08-63	139452	Bearing: 240°		1	0.02	1.5	23	78	71
8V3008RA/RJ	T08-63	139453			1	0.04	2.0	43	43	101
8V3008RA/RJ	T08-63	139454			1	0.03	1.9	78	47	173
8V3008RA/RJ	T08-63	139455			1	0.03	1.9	36	68	144
8V3008RA/RJ	T08-63	139456			1	0.04	2.1	42	71	221
8V3008RA/RJ	T08-63	139457			1	0.04	1.8	15	55	160
8V3008RA/RJ	T08-63	139458	435083	6222248	1	0.03	1.3	11	24	87

8

T08-64 (Anaconda)										
8V3008RA/RJ	T08-64	139459	435091	6222267	1	0.02	1.3	59	18	114
8V3008RA/RJ	T08-64	139460	Bearing: 200°		1	0.01	1.6	36	20	64
8V3008RA/RJ	T08-64	139461			1	0.01	2.1	42	25	95
8V3008RA/RJ	T08-64	139462			1	0.04	2.5	71	31	108
8V3008RA/RJ	T08-64	139463			1	0.02	3.1	57	33	77
8V3008RA/RJ	T08-64	139464			1	0.01	2.1	36	22	65
8V3008RA/RJ	T08-64	139465			435089	6222260	1	0.03	2.3	48

7

T08-65 (Anaconda)										
8V3008RA/RJ	T08-65	139466	435091	6222279	1	0.04	2.7	46	67	121
8V3008RA/RJ	T08-65	139467	Bearing: 195°		1	0.03	1.1	68	47	73
8V3008RA/RJ	T08-65	139468			1	0.02	1.4	7	36	23
8V3008RA/RJ	T08-65	139469	435090	6222275	1	0.01	0.6	19	17	35

Dilworth Surface Chip Samples - 2008

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
--------------------	---------------	---------------	---------------	----------------	-----------	--------	--------	--------	--------	--------

4

T08-66 (Gerry's)

8V3063RA/RJ	T08-66	139435	435012	6223474	1	1.99	7.2	<1	924	3260
8V3063RA/RJ	T08-66	139436	Bearing: 160°		1	1.47	15.9	<1	1672	3109
8V3063RA/RJ	T08-66	139437			1	0.41	9.2	113	1008	12200
8V3063RA/RJ	T08-66	139438			1	0.39	2.3	80	1399	8359
8V3063RA/RJ	T08-66	139439			1	0.08	0.8	<1	266	860
8V3063RA/RJ	T08-66	139440			1	0.49	19.7	152	12300	1949
8V3063RA/RJ	T08-66	139441			1	1.67	136.0	723	33800	9751
8V3063RA/RJ	T08-66	139442			1	1.42	34.0	1268	2219	20900
8V3063RA/RJ	T08-66	139443			1	1.06	69.3	4287	13500	24400
8V3063RA/RJ	T08-66	139444			435015	6223465	1	2.31	39.4	759

10

T08-67 (Sparky)

8V3063RA/RJ	T08-67	139445	435301	6222535	1	0.12	6.1	67	548	664
8V3063RA/RJ	T08-67	139446	Bearing:148°		1	0.11	3.1	16	89	42
8V3063RA/RJ	T08-67	139447			1	0.23	4.2	20	269	127
8V3063RA/RJ	T08-67	139448			1	0.21	5.0	7	46	35
8V3063RA/RJ	T08-67	139449			1	0.23	4.9	7	50	24
8V3063RA/RJ	T08-68	139450	435304	6222530	1	0.01	0.3	10	5	122

6

T08-68 (Sparky)

8V3063RA/RJ	T08-68	139470	435395	6222477	1	0.03	0.7	14	18	68
8V3063RA/RJ	T08-68	139471	Bearing 120°		1	0.04	0.5	12	6	62
8V3063RA/RJ	T08-68	139472			1	0.07	0.7	8	19	33
8V3063RA/RJ	T08-68	139473			1	0.03	0.6	14	13	101
8V3063RA/RJ	T08-68	139474			1	<0.01	0.5	13	14	131
8V3063RA/RJ	T08-68	139475			1	<0.01	0.3	12	6	86
8V3063RA/RJ	T08-68	139476			435401	6222474	1	0.01	0.5	11

7

T08-69 (Annalise)

8V3100RA/RJ	T08-69	139501	434938	6224007	1	11.90	454.8	131	9806	8317		
8V3100RA/RJ	T08-69	139502	Bearing: 290		1	1.28	93.2	88	1231	2459		
8V3100RA/RJ	T08-69	139503			1	0.17	23.2	46	260	431		
8V3100RA/RJ	T08-69	139504			1	0.62	29.3	62	563	1653		
8V3100RA/RJ	T08-69	139505			1	6.67	412.0	86	4930	5180		
8V3100RA/RJ	T08-69	139506			1	0.19	11.7	21	193	282		
8V3100RA/RJ	T08-69	139507			1	1.75	105.0	44	1603	1518		
8V3100RA/RJ	T08-69	139508			1	0.06	1.6	40	28	113		
8V3100RA/RJ	T08-69	139509			1	0.08	2.7	69	39	81		
8V3100RA/RJ	T08-69	139510			1	0.02	0.7	70	11	131		
8V3100RA/RJ	T08-69	139511			1	0.04	0.6	61	6	194		
8V3100RA/RJ	T08-69	139512			1	0.35	2.5	28	48	33		
8V3100RA/RJ	T08-69	139513			1	0.04	1.6	48	60	71		
8V3100RA/RJ	T08-69	139514			1	0.26	2.6	19	41	49		
8V3100RA/RJ	T08-69	139515			1	0.11	1.9	25	38	38		
8V3100RA/RJ	T08-69	139516			1	0.03	0.8	26	30	45		
8V3100RA/RJ	T08-69	139517			1	0.05	0.7	54	29	186		
8V3100RA/RJ	T08-69	139518			1	0.03	0.8	30	27	86		
8V3100RA/RJ	T08-69	139519			434920	6224013	1	0.14	1.7	33	133	138

19

T08-70 (Big K)

Dilworth Surface Chip Samples - 2008

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V3215RA/RJ	T08-70	139520	434841	6224003	1	0.21	3.0	224	343	1279
8V3215RA/RJ	T08-70	139521	Bearing 272		1	0.70	4.2	226	728	1255
8V3215RA/RJ	T08-70	139522	434838	6224003	1	0.26	7.0	322	2255	7424

3

T08-71 (Big K)

8V3215RA/RJ	T08-71	139523	434787	6224011	1	0.42	4.6	205	1282	314
8V3215RA/RJ	T08-71	139524	Bearing 180		1	0.50	5.0	179	801	252
8V3215RA/RJ	T08-71	139525			1	0.33	4.5	159	1283	473
8V3215RA/RJ	T08-71	139526			1	0.45	3.8	193	587	837
8V3215RA/RJ	T08-71	139527			1	0.37	2.6	110	547	299
8V3215RA/RJ	T08-71	139528			1	0.30	1.9	126	70	255
8V3215RA/RJ	T08-71	139529	434787	6224004	1	0.16	2.4	239	67	480

7

T08-72 (Granduc Road North)

8V3215RA/RJ	T08-72	139478	434620	6226338	1	0.06	1.0	37	45	92
8V3215RA/RJ	T08-72	139479	Bearing 180		1	0.02	0.6	19	16	52
8V3215RA/RJ	T08-72	139480			1	0.04	0.6	20	22	68
8V3215RA/RJ	T08-72	139481			1	0.12	0.3	7	79	78
8V3215RA/RJ	T08-72	139482			1	0.13	0.5	16	72	137
8V3215RA/RJ	T08-72	139483			1	0.04	0.6	7	120	247
8V3215RA/RJ	T08-72	139484			1	0.03	0.6	15	10	49
8V3215RA/RJ	T08-72	139485			1	0.02	0.8	11	11	43
8V3215RA/RJ	T08-72	139486			1	0.05	0.8	54	11	55
8V3215RA/RJ	T08-72	139487			1	0.10	0.9	36	41	380
8V3215RA/RJ	T08-72	139488			1	0.02	1.2	16	15	27
8V3215RA/RJ	T08-72	139489			1	0.01	0.7	13	9	53
8V3283RA/RJ	T08-72	139490			1	0.05	1.0	25	82	177
8V3283RA/RJ	T08-72	139491			1	0.02	0.6	25	12	89
8V3283RA/RJ	T08-72	139492			1	0.08	0.5	27	13	69
8V3283RA/RJ	T08-72	139493			1	0.07	0.3	35	7	102
8V3283RA/RJ	T08-72	139494			1	0.03	0.5	31	12	87
8V3283RA/RJ	T08-72	139495			1	0.05	0.6	19	18	61
8V3283RA/RJ	T08-72	139496			1	0.09	0.8	36	65	69
8V3283RA/RJ	T08-72	139497			1	0.05	0.9	35	300	170
8V3283RA/RJ	T08-72	139498			1	0.02	0.5	21	14	76
8V3283RA/RJ	T08-72	139499			1	0.02	0.4	30	10	107
8V3283RA/RJ	T08-72	139500			1	0.02	0.4	52	27	128
8V3283RA/RJ	T08-72	139530			1	0.07	0.5	26	34	56
8V3283RA/RJ	T08-72	139531			1	0.03	0.5	24	29	59
8V3283RA/RJ	T08-72	139532			1	0.02	0.5	34	20	55
8V3283RA/RJ	T08-72	139533			1	0.02	0.3	31	9	104
8V3283RA/RJ	T08-72	139534			1	0.01	0.4	32	9	89
8V3283RA/RJ	T08-72	139535			1	<0.01	0.2	36	7	82
8V3283RA/RJ	T08-72	139536			1	0.01	0.3	23	50	79
8V3283RA/RJ	T08-72	139537			1	0.01	1.1	32	27	87
8V3283RA/RJ	T08-72	139538			1	0.01	<0.1	25	9	83
8V3283RA/RJ	T08-72	139539			1	0.02	0.3	34	7	79
8V3283RA/RJ	T08-72	139540			434620	6226304	1	0.02	1.1	11

34

T08-73 (Chicago North)

8V3613RA/RJ	T08-73	139541	435098	6224311	1	0.13	<0.1	17	27	62
8V3613RA/RJ	T08-73	139542			1	0.07	0.3	21	24	47

Dilworth Surface Chip Samples - 2008

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V3613RA/RJ	T08-73	139543	Bearing 200°		1	0.12	2.6	14	22	37
8V3613RA/RJ	T08-73	139544			1	0.08	<0.1	10	21	53
8V3613RA/RJ	T08-73	139545			1	0.16	3.8	8	34	45
8V3613RA/RJ	T08-73	139546			1	0.18	3.7	8	30	45
8V3613RA/RJ	T08-73	139547			1	0.05	<0.1	14	23	58
8V3613RA/RJ	T08-73	139548			1	0.29	0.5	18	27	75
8V3613RA/RJ	T08-73	139549			1	0.08	<0.1	16	21	81
8V3613RA/RJ	T08-73	139550			1	0.14	0.5	17	42	88
8V3613RA/RJ	T08-73	139551			1	0.34	14.9	28	89	150
8V3613RA/RJ	T08-73	139552			435094	6224300	1	0.06	<0.1	15

12

Dilworth Rock Grab Sample Analytical - 2008

Certificate Number	Sample Number	Zone	Easting NAD83	Northing NAD83	Sample Type	Au g/t	Ag g/t	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3081RA/RJ	Beach #1		435954	6223402		0.01	<0.1	0.59	60	210	0.5	<0.5	0.36	1	39	62	9	2.93	<0.1	0.29	33	0.06	77	7	0.03	26	1124	33	0.41	<5	3	22	5	<0.01	<10	<10	8	<10	80	7
8V3081RA/RJ	Beach #2		435925	6223415		0.03	0.1	0.45	46	144	<0.5	<0.5	0.27	1	26	83	2	1.83	1	0.24	23	0.04	48	7	0.03	15	975	23	0.21	6	2	18	<5	<0.01	<10	<10	8	<10	49	7
8V2237RA	Bottom	Yellowstone	435010	6223620	Fit	3.57	148.0		46	144	<0.5	<0.5	0.27	1	26	83	2	1.83	1	0.24	23	0.04	48	7	0.03	15	975	23	0.21	6	2	18	<5	<0.01	<10	<10	8	<10	49	7
8V2151RA/RJ	P808-01	49er	435215	6223432		9.58	43.8	0.36	202	129	<0.5	<0.5	0.05	7	3	144	18	3.37	3	0.28	<10	0.04	28	<2	0.01	5	433	26.9	2.05	14	1	5	<5	<0.01	<10	<10	10	<10	899	2
8V2151RA/RJ	P808-02	Oxidential	435265	6222739	Fit	2.00	9.1	0.38	242	133	<0.5	<0.5	0.04	3	1	31	7	2.08	3	0.35	<10	0.03	28	<2	0.01	1	471	90	0.33	99	1	3	<5	<0.01	<10	<10	8	<10	354	1
8V2151RA/RJ	P808-03	Oxidential	435244	6222718	Fit	6.58	6.7	0.53	436	197	<0.5	<0.5	0.06	2	8	24	15	4.66	<0.1	0.44	14	0.04	253	<2	0.01	1	811	141	0.23	96	1	3	<5	<0.01	<10	<10	10	<10	89	3
8V2151RA/RJ	P808-04	Below Summit	434724	6225134		0.29	17.7	0.63	212	43	<0.5	<0.5	0.34	28	9	73	54	6.59	2	0.22	<10	0.35	574	<2	0.01	4	177	2097	5.00	23	1	19	<5	<0.01	<10	<10	23	<10	359	4
8V2151RA/RJ	P808-05	Below Summit	434686	6225136		0.10	13.3	0.14	143	<0.5	<0.5	0.12	6	5	92	28	14.98	<0.1	0.15	<10	0.07	151	<2	0.01	3	193	132	5.00	20	<1	15	<5	<0.01	<10	<10	19	14	223	9	
8V2151RA/RJ	P808-06	Below Summit	434676	6225117		0.13	6.9	0.57	58	74	<0.5	<0.5	0.24	26	8	82	8	4.52	3	0.21	<10	0.42	1480	2	0.01	4	575	1443	3.39	10	1	21	<5	<0.01	<10	<10	19	<10	456.7	3
8V3063RA/RJ	P80807	Beach	436211	6222848	Fit	<0.01	0.3	0.52	15	31	0.5	<0.5	1.27	3	16	20	6	6.54	<1	0.32	12	0.11	257	<2	0.03	8	2442	21	5.00	6	3	50	<5	<0.01	<10	<10	25	<10	233	6
8V3063RA/RJ	P80808	Beach	436190	6222919	Fit	<0.01	<0.1	0.66	8	54	<0.5	<0.5	0.29	2	12	21	7	5.88	<1	0.24	11	0.09	77	<2	0.03	6	2171	16	3.66	<5	2	12	<5	<0.01	<10	<10	26	<10	74	5
8V3063RA/RJ	P80809	Beach	436215	6222982	Fit	0.03	<0.1	0.55	28	23	<0.5	<0.5	0.25	3	38	17	13	7.41	<1	0.33	12	0.07	136	9	0.02	29	1662	39	5.00	5	2	19	<5	<0.01	<10	14	25	<10	167	7
8V3063RA/RJ	P80810	Beach	436254	6223052	Fit	<0.01	<0.1	0.07	5	47	<0.5	<0.5	15.00	<1	5	65	1	0.82	<1	0.05	<10	0.11	919	<2	0.01	7	150	<2	0.11	<5	1	10000	<5	<0.01	<10	<10	3	<10	25	1
8V3063RA/RJ	P80811	Beach	436192	6223184	Fit	0.02	<0.1	0.29	<5	35	<0.5	<0.5	1.84	2	10	45	4	6.4	<1	0.17	11	0.16	308	<2	0.04	5	1387	16	5.00	7	4	98	<5	<0.01	<10	<10	21	<10	53	6
8V3063RA/RJ	P80812	Beach	436185	6223192	Fit	0.01	<0.1	0.52	5	14	<0.5	<0.5	0.35	4	8	42	<1	9.82	<1	0.18	10	0.12	80	2	0.04	7	1321	19	5.00	<5	2	21	<5	<0.01	<10	18	27	11	71	8
8V3063RA/RJ	P80813	Beach	436108	6223315	Fit	0.01	<0.1	0.48	14	75	<0.5	<0.5	1.46	2	19	40	7	3.68	<1	0.2	19	0.16	141	2	0.03	10	3355	13	2.83	5	2	113	<5	<0.01	<10	<10	18	<10	118	9
8V3063RA/RJ	P80814	Beach	436058	6223401	Fit	0.02	0.1	0.29	31	28	<0.5	<0.5	1.92	4	44	32	23	9.05	1	0.15	<10	0.13	356	<2	0.02	18	859	34	5.00	8	3	81	<5	<0.01	<10	12	23	<10	276	10
8V3063RA/RJ	P80815	Beach	436021	6223504	Fit	0.04	0.2	0.37	21	111	<0.5	<0.5	0.03	1	5	46	3	2.79	1	0.21	18	0.05	91	4	0.02	16	578	17	2.34	<5	1	13	<5	<0.01	<10	<10	9	<10	39	5
8V3063RA/RJ	P80816	Beach	435967	6223649	Fit	0.01	0.1	0.68	<5	43	0.5	<0.5	0.42	1	9	41	7	4.85	<1	0.28	17	0.13	91	2	0.02	6	1518	17	3.52	<5	2	28	<5	<0.01	<10	12	25	<10	101	7
8V3063RA/RJ	P80817	Beach	435986	6223785	Fit	<0.01	<0.1	1.31	29	166	<0.5	<0.5	1.51	1	14	47	<1	4.98	<1	0.19	<10	0.84	796	4	0.02	48	893	27	1.94	<5	2	91	<5	<0.01	<10	<10	26	<10	150	3
8V3063RA/RJ	P80818	Troy	435196	6226307	Fit	<0.01	<0.1	0.7	28	106	<0.5	<0.5	2.23	1	12	120	<1	3.42	<1	0.18	<10	0.96	576	<2	0.01	61	787	46	0.04	<5	4	238	<5	<0.01	<10	<10	16	<10	111	2
8V3063RA/RJ	P80819	Troy	435017	6226613	Fit	<0.01	5.2	8.07	36	98	<0.5	<0.5	0.12	3	9	160	100	4.05	<1	0.15	<10	0.44	365	<2	0.01	47	819	1203	0.34	<5	4	22	<5	<0.01	<10	<10	22	<10	791	2
8V3063RA/RJ	P80820	Troy	435007	6226607	Fit	0.02	<0.1	2.22	14	143	0.5	<0.5	0.91	1	21	102	36	4.81	<1	0.21	<10	1.33	352	<2	0.02	97	824	144	0.57	<5	3	93	<5	<0.01	<10	<10	44	<10	286	3
8V3063RA/RJ	P80821	Troy	435007	6226607	Fit	<0.01	<0.1	1.3	9	90	<0.5	<0.5	8.81	<1	11	94	<1	3.36	<1	0.14	<10	1.16	1020	<2	0.01	57	542	30	0.25	<5	2	1467	<5	<0.01	<10	<10	26	<10	99	2
8V3063RA/RJ	P80822	Troy	435007	6226607	Fit	<0.01	<0.1	0.76	49	97	<0.5	<0.5	6.81	<1	11	65	<1	9.45	<1	0.18	<10	2.49	1036	<2	0.02	46	899	28	0.13	<5	4	749	<5	<0.01	<10	<10	19	<10	101	2
8V3063RA/RJ	P80823	Troy	435007	6226607	Fit	<0.01	<0.1	1.44	56	120	0.6	<0.5	1.74	1	16	65	29	4.14	<1	0.23	<10	1	303	<2	0.02	87	774	21	0.26	<5	5	189	<5	<0.01	<10	<10	38	<10	136	2
8V3063RA/RJ	P80824	Troy	435291	6222515	Fit	0.02	0.6	2.28	88	112	<0.5	<0.5	0.35	1	19	19	<1	6.02	<1	0.25	<10	1.05	1340	<2	0.02	2	1840	49	0.53	<5	4	7	<5	<0.01	<10	<10	99	<10	158	4
8V3063RA/RJ	P80825	Troy	435291	6222515	Fit	<0.01	<0.1	0.49	8	134	<0.5	<0.5	0.08	<1	5	41	<1	5.71	<1	0.17	16	0.12	149	<2	0.03	3	898	78	1.72	<5	2	10	6	<0.01	<10	<10	11	<10	102	4
8V3374RA/RJ	P80826		434807	6224740		0.02	0.3	3.4	<5	196	<0.5	<0.5	1.84	1	18	33	23	5.11	<1	0.25	<10	1.05	959	<2	0.01	3	1260	21	2.1	<5	11	112	<5	<0.01	<10	<10	114	<10	113	4
8V3374RA/RJ	P80827		435113	6222532		0.07	1.8	1.14	99	134	<0.5	<0.5	0.21	2	9	21	37	6.65	<1	0.35	<10	0.24	411	<2	0.01	5	1631	42	1.71	<5	3	17	<5	<0.01	<10	<10	32	<10	79	3
8V3374RA/RJ	P80829		434881	6222599		0.02	<0.1	2.47	44	168	<0.5	<0.5	3.02	1	28	90	42	5.79	<1	0.28	<10	2.01	1653	<2	0.04	15	1442	19	0											

DILWORTH PROPERTY SOIL SAMPLING ASSAY DATA - 2008

Certificate Number	Sample Number	Easting	Northing	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm	
8V3190SG/SJ	1782	435647	6221782	16	0.2	2.99	6	87	<0.5	<5	0.03	<1	9	24	9	4.90	<1	0.04	24	0.33	560	2	<0.01	10	630	21	0.06	<5	2	5	<5	0.08	<10	<10	37	<10	80	16	
8V3190SG/SJ	1829	435634	6221829	68	0.3	2.61	18	73	<0.5	<5	0.09	<1	13	24	21	4.26	<1	0.04	10	0.77	550	<2	<0.01	25	687	17	0.04	<5	2	9	<5	0.06	<10	<10	44	<10	95	1	
8V3190SG/SJ	1859	435614	6221859	4	0.9	2.01	13	69	<0.5	<5	0.03	<1	13	23	10	5.20	<1	0.04	<10	0.46	960	<2	<0.01	14	646	20	0.05	<5	1	8	<5	0.06	<10	<10	64	<10	67	2	
8V3190SG/SJ	1882	435612	6221882	10	1.2	3.35	20	48	<0.5	<5	0.02	<1	14	20	17	5.73	<1	0.06	29	0.18	1079	3	0.03	7	1274	31	0.12	<5	1	1	<1	<5	0.05	<10	<10	67	<10	77	11
8V3190SG/SJ	1920	435611	6221920	<1	0.3	1.82	8	64	<0.5	<5	0.02	<1	9	17	7	4.54	<1	0.04	13	0.17	836	3	<0.01	6	671	21	0.05	<5	1	6	<5	0.06	<10	<10	70	<10	48	2	
8V3190SG/SJ	1949	435605	6221949	3	0.3	1.45	6	34	<0.5	<5	0.02	<1	8	16	4	4.79	<1	0.04	19	0.16	688	4	0.01	5	725	40	0.07	<5	1	3	<5	0.13	<10	<10	43	<10	47	22	
8V3190SG/SJ	1979	435619	6221979	20	0.4	2.48	23	131	<0.5	<5	0.22	<1	17	29	20	4.62	<1	0.05	19	0.83	727	<2	<0.01	34	1243	21	0.03	<5	4	13	<5	0.06	<10	<10	49	<10	173	3	
8V3190SG/SJ	2013	435616	6222013	9	0.5	2.39	15	74	<0.5	<5	0.09	<1	16	27	21	4.52	<1	0.04	21	0.78	563	2	<0.01	30	877	22	0.03	<5	3	8	<5	0.06	<10	<10	51	<10	120	4	
8V3190SG/SJ	2042	435603	6222042	12	<0.2	3.80	23	71	<0.5	<5	0.07	<1	16	32	20	6.40	<1	0.04	54	0.52	879	6	<0.01	25	2074	26	0.09	<5	3	4	<5	0.06	<10	19	54	<10	151	7	
8V3190SG/SJ	2075	435597	6222075	12	0.4	1.83	21	71	<0.5	<5	0.22	<1	20	27	35	4.64	<1	0.04	13	0.92	894	<2	<0.01	41	1022	18	<0.01	<5	5	13	<5	0.06	<10	<10	48	<10	126	2	
8V3190SG/SJ	2090	435578	6222090	23	0.6	1.80	26	121	<0.5	<5	0.23	<1	21	27	39	4.96	<1	0.05	14	0.95	1129	<2	<0.01	39	1106	23	<0.01	<5	5	14	<5	0.06	<10	<10	51	<10	128	2	
8V3190SG/SJ	2102	435554	6222102	15	0.4	2.39	21	108	<0.5	<5	0.12	<1	19	31	27	4.78	<1	0.06	13	0.85	997	<2	<0.01	32	1131	21	0.02	<5	3	12	<5	0.06	<10	<10	62	<10	123	1	
8V3190SG/SJ	2107	435506	6222107	28	0.3	2.37	20	84	<0.5	<5	0.20	<1	20	28	23	4.96	<1	0.05	13	0.89	974	<2	<0.01	30	693	22	0.03	<5	3	18	<5	0.08	<10	<10	59	<10	118	2	
8V3190SG/SJ	2109	435528	6222109	27	0.4	2.00	19	67	<0.5	<5	0.11	<1	19	24	24	5.23	<1	0.05	14	0.81	1038	<2	<0.01	26	1221	25	0.02	<5	3	11	<5	0.08	<10	<10	58	<10	117	3	
8V3190SG/SJ	2112	435480	6222112	6	0.3	2.28	24	65	<0.5	<5	0.10	<1	13	22	17	4.63	<1	0.04	12	0.67	483	<2	<0.01	17	788	24	0.03	<5	2	11	<5	0.08	<10	<10	61	<10	87	2	
8V3190SG/SJ	2114	435448	6222114	3	0.9	1.22	5	52	<0.5	<5	0.09	<1	5	11	13	1.69	<1	0.06	15	0.19	194	2	<0.01	5	1144	60	0.12	<5	1	8	<5	0.06	<10	<10	30	<10	98	2	
8V3190SG/SJ	2127	435424	6222127	<1	0.3	1.63	7	41	<0.5	<5	0.05	<1	6	14	7	2.50	<1	0.05	10	0.22	202	2	<0.01	6	688	26	0.05	<5	1	9	<5	0.06	<10	<10	49	<10	42	1	
8V3190SG/SJ	2145	435414	6222145	11	1.5	1.01	13	54	<0.5	<5	0.01	<1	3	12	4	1.79	<1	0.08	20	0.14	131	2	0.01	2	1078	45	0.05	<5	<1	4	<5	0.05	<10	<10	39	<10	24	1	
8V3190SG/SJ	2169	435399	6222169	41	<0.2	1.97	89	53	<0.5	<5	0.02	1	7	24	17	7.95	<1	0.03	<10	0.39	287	<2	0.01	8	970	22	0.09	<5	1	8	<5	0.06	<10	<10	100	<10	48	3	
8V3190SG/SJ	2196	435385	6222196	7	1.2	1.04	6	40	<0.5	<5	0.01	<1	5	11	3	2.21	<1	0.03	11	0.09	154	<2	0.01	5	691	14	0.06	<5	1	5	<5	0.07	<10	<10	45	<10	27	3	
8V3190SG/SJ	2224	435376	6222224	32	0.8	3.00	38	52	<0.5	<5	0.05	<1	26	26	20	7.37	<1	0.06	16	0.40	2785	4	0.01	11	2260	33	0.10	<5	2	5	<5	0.09	<10	11	67	<10	89	5	
8V3190SG/SJ	2254	435360	6222254	119	1.1	3.38	30	69	<0.5	<5	0.14	<1	38	31	45	7.48	<1	0.08	39	0.62	3475	2	0.02	16	2148	54	0.07	<5	4	8	<5	0.15	<10	10	88	<10	161	7	
8V3190SG/SJ	2281	435356	6222281	21	<0.2	2.17	16	47	<0.5	<5	0.02	<1	6	27	6	3.80	<1	0.04	15	0.37	197	<2	0.01	12	613	20	0.04	<5	1	8	<5	0.07	<10	<10	71	<10	47	2	
8V3190SG/SJ	2303	435334	6222303	96	2.5	1.91	40	35	<0.5	<5	0.02	1	6	16	9	3.87	<1	0.03	<10	0.30	227	<2	0.01	10	937	15	0.08	<5	<1	6	<5	0.05	<10	<10	42	<10	44	1	
8V3190SG/SJ	2324	435338	6222324	8	3.2	1.88	268	65	<0.5	<5	0.01	5	43	16	21	9.91	<1	0.04	<10	0.21	3910	<2	0.01	3	2323	106	0.09	<5	1	3	<5	0.05	<10	20	111	<10	75	3	
8V3190SG/SJ	2348	435352	6222348	28	0.5	2.03	14	59	<0.5	<5	0.10	<1	10	27	13	4.06	<1	0.04	13	0.72	387	<2	0.01	20	885	23	0.02	<5	2	12	<5	0.08	<10	<10	63	<10	86	2	
8V3190SG/SJ	2371	435345	6222371	110	1.4	2.66	66	87	<0.5	<5	0.12	1	16	27	28	5.95	<1	0.06	19	0.82	926	7	0.01	22	1499	48	0.04	<5	3	11	<5	0.10	<10	<10	69	<10	124	4	
8V3190SG/SJ	2396	435354	6222396	42	0.9	2.17	41	114	<0.5	<5	0.27	1	21	28	37	5.54	<1	0.07	19	1.04	1130	<2	0.01	35	1328	41	0.01	<5	5	16	<5	0.08	<10	12	60	<10	161	3	
8V3190SG/SJ	2422	435356	6222422	510	6.7	1.60	289	56	<0.5	<5	<0.01	5	13	17	28	11.34	<1	0.09	16	0.47	1139	<2	0.01	5	3047	149	0.08	<5	3	3	<5	0.06	<10	13	72	<10	110	5	
8V3190SG/SJ	2443	435356	6222443	33	2.2	2.53	72	156	<0.5	<5	0.34	4	31	25	44	6.23	<1	0.08	29	0.96	2204	<2	0.02	30	1459	101	0.05	<5	4	19	<5	0.06	<10	12	60	<10	520	3	
8V3190SG/SJ	2465	435342	6222465	32	4.3	1.03	67	40	<0.5	<5	0.02	1	4	8	8	2.73	<1	0.06	11	0.06	215	2	0.01	3	997	47	0.08	<5	<1	6	<5	0.06	<10	<10	39	<10	42	1	
8V3190SG/SJ	2470	435333	6222470	5	0.7	1.83	11	47	<0.5	<5	0.08	<1	12	24	11	6.37	<1	0.03	<10	0.51	585	<2	0.01	19	1252	22	0.05	<5	2	11	<5	0.11	<10	<10	69	<10	74	3	
8V3190SG/SJ	2504	435342	6222504	13	3.1	2.18	103	43	<0.5	<5	0.07	2	10	22	21	5.85	<1	0.05	15	0.57	469	<2	0.01	16	1339	145	0.08	<5	1	8	<5	0.07	<10	62	<10	101	5		
8V3190SG/SJ	2532	435339	6222532	7	0.5	3.57	19	35	<0.5	<5	0.03	<1	9	30	17	7.37	<1	0.03	13	0.40	526	<2	0.01	13	1003	26	0.06	<5	2	5	<5	0.09	<10	<10	50	<10	67	8	
8V3190SG/SJ	2549	435328	6222549	41	17.7	3.14	593	54	<0.5	<5	<0.01	11	14	16	22	9.68	<1	0.05	16	0.50	824	<2	0.01	5	1496	102	0.09	5	2	2	<5	0.04	<10	<10	74	<10	116	6	
8V3190SG/SJ	2565	435314	6222565	9	3.5	0.75	268	55	<0.5	<5	<0.01	5	5	4	14	4.23	<1	0.07	17	0.07	222	<2	0.01	2	1089	22	0.04	<5	1	7	<5	0.01	<10	78	<10	64	1		
8V3190SG/SJ	2589	435305	6222589	19	2.9	1.18	361	36	<0.5	<5	<0.01	7	8	12	6	6.76	<1	0.05	15	0.																			

DILWORTH PROPERTY SOIL SAMPLING ASSAY DATA - 2008

Certificate Number	Sample Number	Easting	Northing	Au ppb	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3190SG/SJ	3499	435159	6223499	597	1.9	2.07	2045	55	0.7	<5	0.12	3	23	10	45	7.40	<1	0.03	16	0.65	1478	14	0.01	15	1129	65	0.04	22	3	15	<5	0.06	<10	<10	50	<10	171	7
8V3190SG/SJ	3523	435151	6223523	24	<0.2	2.01	11	70	0.8	<5	0.22	2	12	15	9	4.15	<1	0.04	12	0.65	511	<2	0.01	18	767	13	0.03	<5	2	24	<5	0.09	<10	<10	56	<10	87	3
8V3190SG/SJ	3541	435136	6223541	21	0.2	2.09	18	42	0.8	<5	0.06	2	9	13	2	5.32	<1	0.04	13	0.41	428	3	0.02	9	558	30	0.05	<5	1	11	<5	0.11	<10	<10	53	<10	50	11
8V3190SG/SJ	3565	435126	6223565	30	<0.2	1.75	8	56	0.8	<5	0.21	1	10	12	4	3.88	<1	0.04	12	0.55	467	6	0.02	12	701	12	0.07	<5	1	19	<5	0.09	<10	<10	49	<10	61	5
8V3190SG/SJ	3587	435110	6223587	21	0.2	1.98	10	35	0.6	<5	0.07	1	8	12	6	3.88	1	0.02	10	0.39	331	<2	0.01	11	525	7	0.05	<5	1	16	<5	0.10	<10	<10	55	<10	44	5
8V3190SG/SJ	3612	435111	6223612	27	<0.2	2.34	9	40	0.7	<5	0.10	2	11	15	9	4.95	<1	0.02	10	0.64	442	<2	0.01	15	255	7	0.03	<5	3	18	<5	0.13	<10	<10	60	<10	63	10
8V3190SG/SJ	3634	435105	6223634	15	0.2	2.23	11	14	1.9	<5	0.03	2	5	8	4	5.53	<1	0.06	29	0.12	236	3	0.07	3	446	17	0.06	<5	3	3	9	0.16	<10	<10	24	<10	47	467
8V3190SG/SJ	3660	435097	6223660	27	<0.2	2.42	17	40	0.7	<5	0.09	2	8	18	9	4.82	<1	0.05	21	0.40	317	2	0.02	13	1339	18	0.08	<5	1	11	<5	0.07	<10	<10	52	<10	60	10
8V3190SG/SJ	3685	435086	6223685	30	<0.2	2.08	9	40	0.7	<5	0.10	2	10	15	8	4.72	<1	0.03	11	0.63	399	<2	0.01	16	391	11	0.03	<5	3	19	<5	0.12	<10	<10	57	<10	64	8
8V3190SG/SJ	3702	435067	6223702	156	3.6	2.19	61	17	1.5	<5	0.04	4	7	17	22	8.85	<1	0.05	26	0.25	380	3	0.04	5	687	176	0.08	<5	2	3	5	0.14	<10	<10	41	<10	114	58
8V3190SG/SJ	3723	435040	6223723	36	0.4	0.81	<5	54	<0.5	<5	0.09	<1	2	3	1	0.67	<1	0.04	<10	0.05	35	<2	0.02	1	366	19	0.04	<5	<1	14	<5	0.04	<10	<10	26	<10	8	<1
8V3190SG/SJ	3751	435042	6223751	57	0.5	2.17	17	57	0.8	<5	0.08	2	11	15	6	5.50	<1	0.03	<10	0.56	531	<2	0.01	14	512	12	0.04	<5	2	16	<5	0.12	<10	<10	59	<10	64	5
8V3190SG/SJ	3776	435049	6223776	51	3.6	1.67	28	57	<0.5	<5	0.05	<1	6	9	9	3.21	1	0.05	12	0.29	369	<2	0.01	5	746	17	0.05	<5	1	7	<5	0.03	<10	<10	47	<10	58	1
8V3190SG/SJ	3799	435053	6223799	27	2	1.50	16	34	<0.5	<5	0.05	<1	14	17	11	5.26	<1	0.05	16	0.28	623	4	0.02	10	704	55	0.06	<5	1	5	<5	0.20	<10	<10	68	<10	69	21
8V3190SG/SJ	3826	435059	6223826	63	6	2.01	46	39	<0.5	<5	0.07	1	15	20	29	7.46	<1	0.03	11	0.65	603	<2	0.01	16	593	115	0.04	<5	2	12	<5	0.14	<10	<10	65	<10	102	7
8V3190SG/SJ	3851	435071	6223851	75	7	1.66	50	33	<0.5	<5	0.09	1	9	15	10	4.86	1	0.04	11	0.33	317	3	0.01	6	964	41	0.05	<5	2	9	<5	0.14	<10	<10	77	<10	46	4
8V3190SG/SJ	3880	435051	6223880	24	2.8	2.21	54	44	<0.5	<5	0.04	1	55	14	41	6.73	<1	0.04	13	0.31	4701	3	0.01	3	1119	28	0.09	<5	2	6	<5	0.08	<10	<10	68	<10	42	1
8V3190SG/SJ	3905	435055	6223905	48	11.4	0.94	35	45	<0.5	<5	0.07	1	21	17	16	3.37	<1	0.06	13	0.09	959	3	0.02	3	1087	58	0.08	<5	<1	7	<5	0.06	<10	<10	68	<10	34	1
8V3190SG/SJ	3932	435053	6223932	1809	5.5	1.71	689	57	<0.5	6	<0.01	12	5	13	42	11.69	<1	0.05	12	0.17	396	<2	0.01	<1	1805	72	0.12	<5	1	9	<5	0.04	<10	13	47	<10	74	4
8V3190SG/SJ	3972	435062	6223972	3	0.6	2.02	17	56	<0.5	<5	0.06	<1	14	11	14	5.17	<1	0.05	11	0.77	854	<2	0.01	5	1358	16	0.03	<5	1	3	<5	0.03	<10	<10	50	<10	110	2
8V3190SG/SJ	4027	435073	6224027	237	9.7	2.95	145	87	<0.5	<5	0.08	4	68	14	51	8.13	<1	0.05	77	0.48	2692	5	0.01	10	2147	179	0.11	<5	3	3	<5	0.05	<10	11	43	<10	357	5
8V3190SG/SJ	4046	435086	6224046	141	2.3	0.77	67	35	<0.5	<5	0.01	1	3	5	13	4.37	<1	0.05	<10	0.04	34	4	0.02	<1	800	47	0.07	<5	1	4	<5	0.03	<10	<10	46	<10	28	2
8V3190SG/SJ	4071	435098	6224071	63	4	0.93	33	47	<0.5	<5	0.03	1	4	4	14	2.01	<1	0.07	16	0.12	262	2	0.02	3	1258	42	0.05	<5	<1	3	<5	0.01	<10	<10	27	<10	35	1
8V3190SG/SJ	4108	435115	6224108	132	1.9	1.21	23	59	<0.5	<5	0.01	<1	4	5	5	1.09	<1	0.05	10	0.05	123	2	0.01	1	461	62	0.03	<5	1	3	<5	0.08	<10	<10	42	<10	15	1
8V3190SG/SJ	4128	435128	6224128	135	1.2	1.82	39	61	<0.5	<5	0.11	<1	23	17	43	5.75	<1	0.06	11	0.82	1278	<2	0.01	17	1167	34	0.03	<5	4	8	<5	0.10	<10	<10	53	<10	121	4
8V3190SG/SJ	4153	435131	6224153	494	6.9	2.47	214	106	<0.5	<5	0.14	4	51	18	99	6.96	<1	0.07	20	0.78	2806	<2	0.02	23	2034	71	0.04	<5	5	8	<5	0.06	<10	<10	49	<10	185	4
8V3190SG/SJ	4176	435145	6224176	45	2.2	0.56	51	49	<0.5	<5	0.01	1	2	3	23	2.13	<1	0.06	12	0.03	36	<2	0.01	1	931	35	0.06	<5	<1	4	<5	0.01	<10	<10	36	<10	27	1
8V3190SG/SJ	4203	435141	6224203	369	11.9	0.72	62	50	<0.5	<5	0.05	1	3	4	50	2.53	<1	0.06	11	0.05	82	<2	0.02	3	1309	93	0.09	<5	<1	9	<5	0.01	<10	<10	30	<10	47	1
8V3190SG/SJ	4236	435172	6224236	3	0.4	1.89	9	96	<0.5	<5	0.24	<1	17	21	27	4.67	<1	0.05	13	0.73	781	<2	0.01	21	1153	20	0.02	<5	3	16	<5	0.10	<10	<10	60	<10	104	2
8V3190SG/SJ	4256	435191	6224256	24	1.3	1.75	38	53	<0.5	<5	0.04	1	6	8	8	2.60	<1	0.05	39	0.21	176	5	0.03	2	583	65	0.10	<5	1	<1	<5	0.13	<10	<10	61	<10	52	44
8V3190SG/SJ	4282	435207	6224282	12	0.3	2.01	10	175	<0.5	<5	0.39	<1	19	21	25	4.60	<1	0.04	15	0.81	1153	<2	0.01	25	1371	17	0.03	<5	4	22	<5	0.07	<10	<10	57	<10	126	2
8V3190SG/SJ	4304	435219	6224304	60	1.9	2.30	102	103	<0.5	<5	0.19	2	25	17	33	5.86	<1	0.05	22	0.62	1400	5	0.01	17	1585	29	0.04	<5	4	11	<5	0.10	<10	<10	54	<10	120	6
8V3190SG/SJ	4329	435227	6224329	21	<0.2	2.35	10	90	<0.5	<5	0.16	<1	15	24	28	4.66	<1	0.04	13	0.72	550	<2	0.01	20	1244	27	0.02	<5	3	14	<5	0.08	<10	<10	65	<10	104	2
8V3190SG/SJ	4349	435241	6224349	9	<0.2	1.95	11	144	<0.5	<5	0.34	<1	22	22	41	4.87	<1	0.05	14	0.85	1152	<2	0.01	28	1254	21	<0.01	<5	6	20	<5	0.10	<10	<10	61	<10	127	2
8V2892SG/SJ	2049	435105	6222049	11	0.6	1.79	33	26	<0.5	<5	0.11	1	3	9	8	1.83	<1	0.06	14	0.06	341	3	0.02	3	668	126	0.06	<5	1	4	<5	0.02	<10	<10	18	<10	79	2
8V2892SG/SJ	2109	435063	6222109	10	4.3	2.91	99	144	<0.5	<5	0.22	1	61	4	55	8.41	<1	0.13	16	0.27	>10000	<2	0.02	3	5911	45	0.20	<5	3	7	<5	0.01	<10	<10	46	<10	145	5
8V2892SG/SJ	2281	435134	6222281	23	2.5	2.65	124	110	<0.5	<5	0.11	2	38	5	74	6.95	<1	0.12	16	0.39	3124	<2	0.02	3	2360	58	0.23	<5	1	4	<							

DILWORTH PROPERTY SOIL SAMPLING ASSAY DATA - 2008

Certificate Number	Sample Number	Easting	Northing	Au ppb	Ag ppb	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V28925G/SJ	3090	435182	6223090	1173	43.1	1.55	2710	62	<0.5	<5	0.10	47	20	6	296	11.75	<1	0.10	11	0.20	3821	70	0.01	1	8601	2179	0.12	<5	1	5	<5	0.02	<10	13	75	<10	320	7
8V28925G/SJ	3117	435179	6223117	294	2.9	1.80	268	187	<0.5	<5	0.47	9	24	13	267	6.08	<1	0.09	18	0.56	2677	51	0.02	13	1786	159	0.09	<5	2	24	<5	0.04	<10	<10	44	<10	460	5
8V28925G/SJ	3144	435160	6223144	278	35.6	1.95	285	128	<0.5	<5	0.01	5	9	6	108	6.85	<1	0.08	10	0.07	1017	109	0.01	1	1221	341	0.07	<5	1	1	<5	0.03	<10	<10	64	<10	185	3
8V28925G/SJ	3176	435158	6223176	302	4.2	2.92	300	85	<0.5	<5	0.09	5	19	24	166	6.71	<1	0.07	15	0.67	1674	17	0.01	20	1888	110	0.05	<5	4	4	<5	0.05	<10	<10	49	<10	177	7
8V28925G/SJ	3185	435132	6223185	545	18.6	2.09	634	109	<0.5	7	0.03	12	37	25	306	11.19	<1	0.07	<10	1.17	9785	45	0.01	2	5377	1882	0.14	<5	5	2	<5	0.01	<10	56	87	<10	530	8
8V28925G/SJ	3225	435108	6223225	332	4.1	2.02	224	210	1	<5	0.52	20	31	20	770	6.76	<1	0.09	49	0.79	4565	18	0.01	29	2029	304	0.12	<5	13	16	<5	0.02	<10	19	51	17	1475	6
8V28925G/SJ	3244	435089	6223244	381	2.7	1.51	239	51	<0.5	<5	0.05	3	14	70	98	12.58	<1	0.05	<10	0.14	1437	112	0.01	<1	3873	114	0.05	<5	5	3	<5	0.21	<10	<10	483	<10	55	7
8V28925G/SJ	3264	435093	6223264	478	5.1	2.59	82	61	<0.5	<5	0.05	2	22	18	207	6.76	<1	0.10	22	0.20	3961	59	0.02	4	2415	194	0.08	<5	3	1	<5	0.05	<10	10	65	12	286	7
8V28925G/SJ	3293	435083	6223293	425	3.4	1.39	850	92	<0.5	7	0.01	15	32	4	215	10.91	<1	0.06	<10	0.30	6869	30	0.01	<1	3783	1076	0.08	<5	1	1	<5	0.01	<10	31	96	<10	374	4
8V28925G/SJ	3328	435085	6223328	462	63.8	0.80	1675	106	<0.5	<5	0.07	37	22	1	275	7.26	<1	0.08	14	0.40	4408	25	0.01	<1	1048	1526	0.07	6	2	2	<5	0.01	<10	16	29	<10	724	3
8V28925G/SJ	3389	435026	6223389	837	4.9	1.86	1331	62	<0.5	5	0.01	23	37	7	245	10.34	<1	0.07	<10	0.60	6100	20	0.01	1	1820	609	0.06	<5	5	1	<5	0.02	<10	26	105	<10	202	5
8V28925G/SJ	3405	435022	6223405	235	9.3	1.50	316	45	<0.5	<5	0.06	7	23	4	208	7.76	<1	0.09	<10	0.56	4758	8	0.01	1	1334	1853	0.10	<5	4	1	<5	0.01	<10	17	70	<10	546	3
8V28925G/SJ	3449	435002	6223449	143	3.2	1.82	207	67	<0.5	<5	0.31	5	27	16	83	6.00	<1	0.07	11	0.85	1722	9	0.01	17	1203	412	0.06	<5	3	11	<5	0.05	<10	<10	57	<10	334	3
8V28925G/SJ	3464	434980	6223464	386	2.6	0.64	189	89	<0.5	<5	0.06	4	4	1	17	1.00	<1	0.05	<10	0.05	165	3	0.01	<1	383	32	0.03	<5	1	2	<5	0.01	<10	<10	45	<10	45	<1
8V28925G/SJ	3488	434957	6223488	116	3.1	1.45	62	107	<0.5	<5	0.41	2	9	6	54	3.99	<1	0.10	<10	0.27	1199	19	0.02	12	1151	556	0.13	<5	1	10	<5	0.03	<10	<10	63	<10	216	1
8V28925G/SJ	3500	434931	6223500	86	1.0	0.47	53	53	<0.5	<5	0.04	1	5	1	13	0.81	<1	0.08	<10	0.03	134	<2	0.01	<1	316	7	0.02	<5	<1	1	<5	0.01	<10	<10	17	<10	22	<1
8V28925G/SJ	3523	434922	6223523	96	4.0	2.19	106	69	<0.5	<5	0.07	2	15	7	82	6.22	<1	0.07	<10	0.36	1633	19	0.01	1	1266	177	0.10	<5	1	9	<5	0.05	<10	<10	145	<10	158	2
8V28925G/SJ	3549	434925	6223549	76	<0.2	2.31	23	62	<0.5	<5	0.07	<1	13	32	48	5.40	<1	0.06	10	0.78	707	10	0.01	40	811	29	0.06	<5	2	9	<5	0.05	<10	<10	68	<10	142	2
8V28925G/SJ	3572	434931	6223572	32	1.1	3.07	15	24	<0.5	<5	0.04	<1	5	18	16	6.81	<1	0.07	25	0.09	477	29	0.06	1	765	39	0.09	<5	1	<1	5	0.12	<10	<10	24	<10	77	157
8V28925G/SJ	3596	434945	6223596	490	2.7	1.84	402	127	<0.5	<5	0.12	10	36	4	67	7.05	<1	0.14	14	0.53	4987	14	0.01	3	1681	176	0.03	<5	2	3	<5	0.02	<10	17	36	<10	335	3
8V28925G/SJ	3622	434945	6223622	56	0.7	2.65	36	70	<0.5	<5	0.15	<1	24	26	35	5.82	<1	0.04	13	0.93	1542	3	0.01	27	686	26	0.04	<5	3	8	<5	0.07	<10	<10	63	<10	194	3
8V28925G/SJ	3648	434940	6223648	120	1.9	1.83	161	71	<0.5	<5	0.06	2	12	15	23	6.04	<1	0.10	<10	0.20	2896	23	0.01	3	1493	677	0.11	<5	<1	4	<5	0.05	<10	10	65	<10	307	2
8V28925G/SJ	3668	434945	6223668	376	2.3	1.98	543	73	<0.5	<5	0.05	8	39	2	92	9.79	<1	0.13	14	0.68	4116	11	0.01	<1	2900	192	0.09	<5	3	1	<5	0.08	<10	17	51	<10	111	3
8V28925G/SJ	3699	434945	6223699	856	3.2	1.81	352	75	<0.5	<5	0.08	8	46	2	400	9.38	<1	0.11	15	0.85	4938	43	0.01	1	2356	67	0.14	<5	6	1	<5	0.10	<10	19	54	<10	366	3
8V28925G/SJ	3712	434945	6223712	455	5.2	2.17	382	131	<0.5	<5	0.10	9	54	4	492	8.96	<1	0.13	16	1.05	5328	50	0.01	4	1849	123	0.06	<5	6	2	<5	0.09	<10	20	82	<10	347	3
8V28925G/SJ	3737	434933	6223737	149	3.2	1.83	107	47	<0.5	<5	0.04	2	8	21	114	6.16	<1	0.05	<10	0.28	449	27	0.01	9	590	748	0.04	<5	2	5	<5	0.03	<10	<10	80	<10	265	2
8V28925G/SJ	3762	434927	6223762	8	1.2	2.97	26	109	<0.5	<5	0.32	<1	20	2	122	6.85	<1	0.11	<10	1.32	1915	2	0.01	3	1185	58	0.05	<5	3	10	<5	0.01	<10	<10	93	<10	177	3
8V28925G/SJ	3783	434920	6223783	85	2.7	1.54	85	92	<0.5	6	0.01	<1	39	2	80	10.34	<1	0.08	12	1.13	5371	<2	0.01	<1	2122	123	0.07	<5	3	1	<5	<0.01	<10	23	42	<10	133	5
8V28925G/SJ	3837	434917	6223837	8	<0.2	0.31	9	199	<0.5	<5	1.37	1	2	2	22	0.52	<1	0.06	<10	0.05	115	<2	0.03	9	1008	20	0.16	<5	1	73	<5	0.01	<10	6	<10	84	1	
8V28925G/SJ	3862	434933	6223862	583	12.2	1.69	381	104	<0.5	<5	0.27	9	13	14	62	6.03	<1	0.10	13	0.36	1386	3	0.01	12	1250	782	0.06	7	2	14	<5	0.02	<10	<10	32	<10	668	3
8V28925G/SJ	3886	434969	6223886	187	18.3	3.14	170	100	<0.5	<5	0.28	4	37	27	41	6.23	<1	0.08	20	0.87	2466	<2	0.03	29	1484	223	0.04	<5	4	16	<5	0.08	<10	<10	58	<10	539	3
8V28925G/SJ	3914	434965	6223914	556	6.2	1.85	209	511	<0.5	7	0.38	3	30	4	45	6.45	<1	0.07	18	0.69	5866	2	0.01	3	1952	40	0.25	<5	3	18	<5	0.01	<10	22	27	<10	130	4
8V28925G/SJ	3946	434962	6223946	4	1.5	2.86	14																															

DILWORTH PROPERTY SOIL SAMPLING ASSAY DATA - 2008

Certificate Number	Sample Number	Easting	Northing	Au ppb	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V28925G/SJ	4760	435012	6224760	3	0.6	1.81	10	115	<0.5	<5	0.07	<1	43	12	14	6.70	<1	0.07	10	0.20	4934	<2	0.02	2	2197	37	0.10	<5	1	4	<5	0.01	<10	19	70	<10	53	2
8V28925G/SJ	4781	435010	6224781	2	0.2	1.69	15	75	<0.5	<5	0.03	<1	14	41	16	4.83	<1	0.05	14	0.71	453	<2	0.01	42	629	19	0.03	<5	2	4	<5	0.01	<10	<10	38	<10	91	3
8V28925G/SJ	4805	435014	6224805	5	<0.2	1.19	10	61	<0.5	<5	0.07	<1	14	30	15	4.48	<1	0.04	10	0.47	724	<2	0.01	29	1169	14	0.06	<5	2	5	<5	0.01	<10	<10	30	<10	69	2
8V28925G/SJ	4830	435004	6224830	<1	<0.2	2.45	48	43	<0.5	<5	0.38	<1	20	29	14	3.94	<1	0.06	<10	0.59	2151	3	0.02	28	774	14	0.06	<5	2	36	<5	0.06	<10	<10	52	<10	107	2
8V28925G/SJ	4847	434993	6224847	4	<0.2	2.95	106	268	<0.5	<5	0.10	2	13	26	10	4.20	<1	0.06	12	0.50	3727	3	0.01	15	1668	18	0.16	<5	1	9	<5	0.06	<10	13	61	<10	119	2
8V28925G/SJ	4865	434981	6224865	5	<0.2	1.81	10	86	<0.5	<5	0.41	<1	6	43	11	3.33	<1	0.05	<10	0.65	267	<2	0.01	39	780	10	0.04	<5	1	26	<5	0.02	<10	<10	36	<10	67	3
8V28925G/SJ	4890	434971	6224890	8	<0.2	1.94	16	161	<0.5	<5	0.32	<1	23	39	21	4.69	<1	0.12	12	0.68	2150	<2	0.02	49	932	26	0.06	<5	2	20	<5	0.02	<10	<10	42	<10	166	3
8V28925G/SJ	4902	434966	6224902	1	<0.2	0.65	<5	76	<0.5	<5	0.03	<1	4	3	2	0.45	<1	0.07	<10	0.04	26	<2	0.01	<1	229	9	0.02	<5	1	7	<5	0.07	<10	<10	31	<10	8	<1
8V28925G/SJ	4916	434949	6224916	7	<0.2	1.33	9	119	<0.5	<5	0.08	<1	4	40	8	3.07	<1	0.08	12	0.51	97	<2	0.01	35	700	19	0.03	<5	2	7	<5	0.01	<10	<10	35	<10	55	2
8V28925G/SJ	4936	434941	6224936	8	<0.2	0.90	6	64	<0.5	<5	0.07	<1	4	24	9	2.18	<1	0.06	10	0.28	90	<2	0.01	18	701	12	0.04	<5	1	6	<5	0.02	<10	<10	25	<10	38	1
8V28925G/SJ	1979	435141	6221979	65	4.7	3.20	1076	29	<0.5	<5	0.06	20	12	9	36	6.07	<1	0.06	47	0.11	1738	2	0.03	<1	788	76	0.10	8	3	<1	<5	0.08	<10	<10	17	<10	154	41
8V28925G/SJ	2006	435127	6222006	13	2.7	1.95	32	34	<0.5	<5	0.05	<1	7	15	14	3.43	<1	0.05	12	0.17	426	3	0.01	4	1103	23	0.12	<5	1	5	<5	0.07	<10	<10	57	<10	48	4
8V28925G/SJ	2023	435108	6222023	29320	18.9	1.64	260	109	<0.5	<5	0.03	4	6	2	24	4.48	1	0.06	11	0.14	1042	<2	0.01	<1	1071	39	0.06	<5	3	2	<5	0.01	<10	<10	144	<10	40	2
8V28925G/SJ	2072	435082	6222072	24	0.5	1.07	67	59	<0.5	<5	0.02	1	4	2	7	1.08	<1	0.07	15	0.06	85	<2	0.01	1	524	7	0.04	<5	1	2	<5	0.01	<10	<10	19	<10	21	1
8V28925G/SJ	2094	435079	6222094	107	2.8	1.74	2050	83	<0.5	<5	0.20	38	14	4	10	4.45	<1	0.09	27	0.31	2133	<2	0.01	<1	1376	57	0.08	6	1	5	<5	0.01	<10	<10	20	<10	164	3
8V28925G/SJ	2136	435057	6222136	375	0.6	1.57	600	59	<0.5	5	0.03	10	35	3	36	7.60	<1	0.12	15	0.35	5009	<2	0.01	1	2419	121	0.07	<5	1	1	<5	0.01	<10	19	45	<10	114	3
8V28925G/SJ	2152	435031	6222152	24	1.9	1.39	256	216	<0.5	5	0.08	5	40	6	19	4.95	<1	0.12	<10	0.19	8190	2	0.01	4	2140	85	0.14	<5	<1	5	<5	0.01	<10	<10	35	<10	107	<1
8V28925G/SJ	2180	435020	6222180	71	3.0	1.79	582	73	<0.5	<5	0.16	10	18	21	30	6.33	<1	0.10	10	0.58	1482	<2	0.01	4	2222	99	0.12	<5	1	6	<5	0.01	<10	<10	72	<10	177	3
8V28925G/SJ	2209	435015	6222209	12	0.9	1.61	121	88	<0.5	<5	0.07	2	6	17	15	2.73	<1	0.05	<10	0.21	274	<2	0.01	3	596	14	0.06	<5	1	3	<5	0.03	<10	<10	80	<10	26	1
8V28925G/SJ	2233	435027	6222233	31	1.0	1.35	68	63	<0.5	<5	0.03	1	4	16	16	2.60	<1	0.08	<10	0.12	149	<2	0.01	1	984	22	0.08	<5	1	1	<5	0.05	<10	<10	88	<10	19	1
8V28925G/SJ	2256	435036	6222256	24	0.7	1.40	839	65	<0.5	<5	0.14	15	12	13	5	5.66	<1	0.08	17	0.14	1947	4	0.02	5	1164	42	0.11	<5	1	7	<5	0.09	<10	<10	52	<10	98	5
8V28925G/SJ	2281	435047	6222281	39	1.1	2.30	49	43	<0.5	<5	0.06	<1	11	28	13	4.58	<1	0.05	10	0.30	577	2	0.01	10	850	34	0.09	<5	2	5	<5	0.10	<10	<10	66	<10	48	5
8V28925G/SJ	2300	435050	6222300	66	0.4	1.31	46	56	<0.5	<5	0.04	1	3	6	5	1.13	<1	0.05	<10	0.07	53	<2	0.01	2	692	25	0.07	<5	<1	3	<5	0.03	<10	<10	47	<10	18	1
8V28925G/SJ	2332	435049	6222332	341	<0.2	1.49	1092	47	<0.5	<5	0.02	20	14	3	19	7.67	<1	0.07	<10	0.13	995	<2	0.01	<1	628	90	0.05	<5	1	1	<5	0.08	<10	<10	48	<10	47	3
8V28925G/SJ	2362	435047	6222362	20	<0.2	0.78	6	43	<0.5	<5	0.06	<1	15	20	7	1.35	<1	0.04	<10	0.07	56	4	0.01	3	719	47	0.08	6	1	7	<5	0.34	<10	<10	101	<10	21	7
8V28925G/SJ	2387	435063	6222387	27	0.6	1.64	93	139	<0.5	<5	0.12	1	21	6	22	5.21	<1	0.08	<10	0.36	2372	<2	0.01	3	934	38	0.22	<5	1	6	<5	0.04	<10	<10	87	<10	74	2
8V28925G/SJ	2405	435065	6222405	1896	3.8	2.26	1173	105	<0.5	6	0.12	22	46	2	155	10.30	<1	0.11	12	0.54	4495	<2	0.01	2	1528	198	0.17	<5	4	3	<5	0.01	<10	<10	75	<10	180	4
8V28925G/SJ	2425	435075	6222425	175	1.4	2.32	202	87	<0.5	<5	0.18	3	30	3	53	6.23	<1	0.13	11	0.64	3672	2	0.01	2	1258	137	0.16	<5	3	5	<5	0.01	<10	13	60	<10	190	3
8V28925G/SJ	2451	435097	6222451	522	6.7	2.25	596	230	1.5	17	0.06	14	60	4	212	8.74	<1	0.10	27	0.34	8975	8	0.01	4	2331	377	0.16	<5	7	1	<5	0.01	<10	44	43	<10	556	4
8V28925G/SJ	2469	435124	6222469	1288	4.2	2.20	874	61	<0.5	<5	0.18	15	32	9	52	6.42	<1	0.10	15	0.31	3115	2	0.01	5	1041	71	0.05	<5	2	2	<5	0.02	<10	<10	54	<10	117	3
8V28925G/SJ	2489	435116	6222489	503	5.8	2.41	745	64	<0.5	<5	0.07	13	28	6	70	7.76	<1	0.10	12	0.21	2774	<2	0.01	2	1262	78	0.06	<5	2	1	<5	0.01	<10	<10	75	<10	99	6
8V28925G/SJ	2494	435131	6222494	474	5.7	2.43	653	58	<0.5	5	0.01	11	34	4	77	8.41	<1	0.09	10	0.24	3390	<2	0.01	<1	1382	69	0.05	<5	3	1	<5	0.01	<10	13	80	<10	76	4
8V28925G/SJ	2524	435147	6222524	194	7.6	1.90	442	62	<0.5	<5	0.03	6	26	7	40	6.34	<1	0.07	10	0.27	2528	<2	0.01	2	1114	56	0.07	<5	2	2	<5	0.01	<10	<10	61	<10	66	3
8V28925G/SJ	2552	435159	6222552	49	3.4	1.38	325	51	<0.5	<5	0.03	6	6	8	12	3.25	<1	0.07	17	0.13	613	<2	0.01	2	1093	66	0.07	<5	<1	3	<5	0.02	<10	<10	44	<10	61	1
8V28925G/SJ	2578	435167	6222578	47	0.5	0.83	26	54	<0.5	<5	0.05	1	4	6	7	1.10	<1	0.05	10	0.08	90	<2	0.01	1	460	45	0.04	<5	1	6	<5	0.04	<10	<10	31	<10	26	1
8V28925G/SJ	2644	435165	6222644	4826	154.5	0.32	1751	45	<0.5	<5	0.06	35	15	<1	210	7.29	<1	0.11	19	0.02	2146	<2	0.01	<1	1602	5256	0.11	78	2	6	<5	<0.01	<10	<10	6	<10	1029	3
8V28925G/SJ	2667	435154	6222667	163	2.7	1.70	557	72	<0.5	<5	0.01	10	16	10	57	1																						

DILWORTH PROPERTY SOIL SAMPLING ASSAY DATA - 2008

Certificate Number	Sample Number	Easting	Northing	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V28925G/SJ	3486	434828	6223486	252	34.4	2.11	701	90	<0.5	<5	0.06	13	89	37	214	9.29	<1	0.08	<10	0.51	>10000	84	0.02	7	2640	1018	0.15	<5	3	4	<5	0.04	<10	40	204	<10	246	4
8V28925G/SJ	3515	434819	6223515	632	12.0	1.71	726	203	<0.5	<5	0.68	30	64	12	350	9.03	<1	0.10	20	0.37	9506	92	0.03	7	2116	1535	0.12	<5	3	18	<5	0.01	<10	36	68	13	1160	5
8V28925G/SJ	3534	434802	6223534	670	7.8	2.69	869	121	<0.5	<5	0.03	15	43	46	177	8.56	<1	0.05	11	0.50	9412	95	0.01	7	1698	342	0.10	<5	7	1	<5	0.07	<10	35	261	12	359	3
8V28925G/SJ	3567	434791	6223567	242	4.3	1.92	136	57	<0.5	<5	0.04	2	25	7	50	7.48	<1	0.07	<10	0.28	7786	31	0.02	3	3392	302	0.09	<5	1	6	<5	0.03	<10	27	89	<10	98	3
8V28925G/SJ	3590	434791	6223590	703	12.2	1.81	627	54	<0.5	5	0.06	18	56	3	377	10.90	<1	0.08	<10	0.21	8596	67	0.03	1	2677	3118	0.16	<5	4	1	<5	0.01	<10	31	37	<10	674	6
8V28925G/SJ	3617	434790	6223617	273	5.4	1.07	358	179	<0.5	<5	0.22	9	11	4	135	5.56	<1	0.06	10	0.15	4274	94	0.01	1	1748	831	0.05	<5	2	6	<5	0.01	<10	12	25	<10	513	4
8V28925G/SJ	3639	434780	6223639	100	11.4	1.58	228	184	<0.5	<5	0.22	30	34	44	183	6.61	<1	0.07	<10	0.23	>10000	449	0.02	15	2630	9414	0.21	<5	1	9	<5	0.06	<10	73	87	11	1030	3
8V28925G/SJ	3659	434770	6223659	45	1.2	1.00	326	120	<0.5	<5	0.02	5	14	3	65	7.94	<1	0.05	<10	0.06	581	38	0.02	1	1407	115	0.05	<5	1	2	<5	0.03	<10	<10	167	<10	132	3
8V28925G/SJ	3685	434782	6223685	340	2.9	1.18	57	56	<0.5	<5	0.04	1	6	6	20	3.46	<1	0.05	<10	0.27	810	28	0.01	3	929	163	0.05	<5	<1	3	<5	0.03	<10	<10	56	<10	108	2
8V28925G/SJ	3712	434789	6223712	434	2.6	1.04	110	63	<0.5	<5	0.03	2	7	4	31	4.54	<1	0.07	<10	0.10	858	43	0.01	1	1568	73	0.08	<5	<1	2	<5	0.02	<10	<10	60	<10	51	2
8V28925G/SJ	3736	434786	6223736	628	12.7	2.94	204	165	<0.5	<5	0.76	18	43	16	1583	7.59	<1	0.13	117	0.49	5714	56	0.02	9	3167	1866	0.31	<5	16	21	<5	0.03	<10	19	50	13	1615	13
8V28925G/SJ	3759	434776	6223759	67	3.8	1.21	259	169	<0.5	<5	0.06	6	39	4	53	8.13	<1	0.09	<10	0.12	8920	75	0.01	2	3835	705	0.12	<5	1	3	<5	0.01	<10	32	60	<10	524	5
8V28925G/SJ	3786	434779	6223786	1209	9.3	1.99	709	137	<0.5	5	0.03	24	93	4	460	12.56	<1	0.08	11	0.45	>10000	186	0.01	3	2907	2128	0.11	<5	13	<1	5	0.02	<10	55	57	12	1050	7
8V28925G/SJ	3813	434780	6223813	170	4.3	3.00	115	104	<0.5	<5	0.51	6	63	10	704	6.12	<1	0.07	68	0.29	5404	61	0.01	5	1775	1989	0.15	<5	2	20	<5	0.02	<10	17	63	<10	616	3
8V28925G/SJ	3839	434788	6223839	187	2.5	2.61	22	28	<0.5	<5	0.06	<1	5	18	101	5.62	<1	0.05	27	0.05	250	48	0.03	<1	813	383	0.11	<5	1	<1	<5	0.13	<10	<10	32	<10	80	204
8V28925G/SJ	3866	434789	6223866	210	2.5	1.62	89	165	<0.5	<5	0.04	2	20	8	61	8.73	<1	0.05	<10	0.16	2147	118	0.01	3	1577	365	0.08	<5	1	4	<5	0.08	<10	<10	139	<10	143	4
8V28925G/SJ	3888	434784	6223888	505	19.5	2.49	688	200	<0.5	13	0.01	97	55	10	453	14.83	<1	0.04	15	0.38	>10000	114	0.01	9	1972	5178	0.15	<5	53	<1	10	0.01	<10	165	54	24	2538	9
8V28925G/SJ	3916	434798	6223916	1680	4.8	1.50	827	67	<0.5	<5	0.03	14	48	1	284	11.67	<1	0.07	11	0.31	5246	54	0.01	<1	1878	455	0.09	<5	4	<1	<5	0.01	<10	15	35	<10	173	7
8V28925G/SJ	3940	434803	6223940	1160	5.4	0.95	1106	151	0.7	9	0.02	30	49	<1	209	13.45	<1	0.08	42	0.35	8752	24	0.01	3	3327	674	0.04	<5	8	<1	<5	<0.01	<10	29	23	<10	467	8
8V28925G/SJ	3961	434800	6223961	371	3.2	2.56	590	75	<0.5	<5	0.04	11	76	<1	634	>15.00	<1	0.08	<10	0.98	6751	59	0.02	<1	4026	136	0.11	<5	10	<1	<5	0.05	<10	19	78	<10	237	9
8V28925G/SJ	3979	434795	6223979	394	3.6	2.12	202	143	<0.5	<5	0.06	8	24	17	316	9.19	1	0.06	13	0.20	5507	177	0.02	5	1580	1809	0.08	<5	2	3	<5	0.04	<10	17	72	18	1912	4
8V28925G/SJ	3991	434814	6223991	440	7.6	2.98	32	78	<0.5	<5	0.04	2	15	11	114	4.02	<1	0.08	10	0.21	1638	51	0.01	2	1396	56	0.09	<5	<1	2	<5	0.02	<10	<10	57	<10	261	2
8V28925G/SJ	4011	434834	6224011	80	1.0	1.66	156	80	<0.5	<5	0.03	2	31	4	68	7.89	<1	0.11	15	0.51	3616	4	0.01	2	2016	280	0.04	<5	5	<1	<5	0.01	<10	<10	38	<10	333	8
8V28925G/SJ	4038	434836	6224038	34	0.7	1.88	111	176	<0.5	<5	0.05	2	9	2	7	5.64	<1	0.08	<10	0.17	974	4	0.01	<1	1098	136	0.06	<5	1	2	<5	0.01	<10	<10	42	<10	165	5
8V28925G/SJ	4060	434837	6224060	15	0.9	1.36	53	334	<0.5	<5	0.38	2	6	5	17	2.53	<1	0.10	<10	0.10	847	7	0.01	2	752	28	0.05	<5	<1	10	<5	0.03	<10	<10	53	<10	46	1
8V28925G/SJ	4079	434849	6224079	53	0.5	1.68	79	118	<0.5	<5	0.15	2	18	8	36	5.58	<1	0.07	24	0.14	1884	14	0.02	1	955	69	0.06	<5	1	4	<5	0.08	<10	<10	58	<10	93	7
8V28925G/SJ	4101	434860	6224101	11	0.7	2.82	50	89	<0.5	<5	0.07	1	12	14	31	5.50	<1	0.09	17	0.35	1198	3	0.02	8	1175	33	0.09	<5	1	2	<5	0.03	<10	<10	51	<10	82	4
8V28925G/SJ	4122	434878	6224122	251	<0.2	2.53	49	43	<0.5	<5	0.05	<1	12	30	27	10.60	<1	0.06	25	0.16	1022	3	0.03	5	1233	92	0.12	<5	2	<1	<5	0.17	<10	<10	57	<10	99	86
8V28925G/SJ	4134	434899	6224134	1452	4.0	2.60	728	111	<0.5	<5	0.05	12	65	27	107	10.56	<1	0.07	17	0.88	8322	<2	0.01	29	2541	131	0.12	<5	7	1	<5	0.04	<10	28	72	<10	294	10
8V28925G/SJ	4155	434914	6224155	23	<0.2	1.49	136	46	<0.5	<5	0.02	2	12	7	20	8.85	<1	0.06	<10	0.18	1000	<2	0.01	<1	1469	30	0.06	<5	1	1	<5	0.01	<10	<10	88	<10	37	6
8V28925G/SJ	4176	434925	6224176	16	2.7	2.76	26	54	<0.5	<5	0.44	1	16	26	70	2.98	<1	0.05	38	0.25	984	4	0.03	14	766	41	0.13	<5	2	11	<5	0.11	<10	<10	27	<10	121	43
8V28925G/SJ	4196	434944	6224196	11	0.2	2.34	350	34	<0.5	<5	0.03	5	25	10	47	11.75	<1	0.02	10	0.29	2784	<2	0.02	2	1383	38	0.11	<5	1	2	<5	0.04	<10	<10	53	<10	108	7
8V28925G/SJ	4214	434964	6224214	323	0.7	2.27	156	58	<0.5	<5	0.04	2	17	25	27	10.47	<1	0.06	16	0.26	2815	3	0.02	6	1614	56	0.11	<5	1	3	<5	0.08	<10	<10	69	<10	97	12
8V28925G/SJ	4238	434978	6224238	258	1.4	2.21	229	58	<0.5	<5	0.02	3	12	4	32	10.37	<1	0.04	<10	0.10	1241	<2	0.01	<1	1845	57	0.07	<5	1	1	<5	0.02	<10	<10	131	<10	50	5
8V28925G/SJ	4272	435008	6224272	110	46.8	1.74	225	48	<0.5	<5	0.09	3	12	4	43	8.22	<1	0.03	10	0.46	756	3	0.01	2	971	559	0.07	<5	2	4	<5	0.01	<10	<10	54	<10	202	4
8V28925G/SJ	4289	435028	6224289	320	8.5	1.88	177	43	<0.5	5	0.08	3	68	3	168	10.89	<1	0.04	17	0.97	3339	<2	0.01	6	2205	120	0.13	<5	5	1	<5	0.01	<10	<10	49	<10	207	5
8V28925G/SJ	4313																																					

DILWORTH PROPERTY SOIL SAMPLING ASSAY DATA - 2008

Certificate Number	Sample Number	Easting	Northing	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm	
8V3613SG/SJ	5000E 2750N	435000	6222750	124	<0.2	1.58	97	113	<0.5	<5	0.16	2	19	22	28	4.95	<1	0.07	17	0.74	1615	2	<0.01	20	1378	63	0.04	11	2	9	<5	0.01	<10	13	95	<10	115	4	
8V3613SG/SJ	5000E 2775N	435000	6222775	9	<0.2	2.65	26	28	<0.5	<5	0.02	<1	7	35	1	9.36	<1	0.05	19	0.09	449	7	<0.01	<1	974	51	0.08	18	2	5	<5	0.24	<10	61	169	<10	50	45	
8V3613SG/SJ	5000E 2800N	435000	6222800	12	<0.2	2.20	37	133	<0.5	<5	0.17	1	18	29	26	7.77	<1	0.07	10	0.43	1751	2	0.01	<1	2313	81	0.06	14	3	6	<5	0.03	<10	<10	316	<10	62	6	
8V3613SG/SJ	5025E 2550N	435025	6222550	1710	11.7	3.14	978	100	<0.5	<5	0.18	28	48	107	92	7.65	<1	0.11	10	1.35	5369	<2	<0.01	5	2180	3691	0.07	38	13	7	<5	0.01	<10	<10	351	<10	307	6	
8V3613SG/SJ	5025E 2575N	435025	6222575	6	<0.2	1.59	21	58	<0.5	<5	0.01	<1	5	7	7	3.00	<1	0.07	16	1.00	290	<2	<0.01	<1	1108	54	0.02	6	2	4	<5	0.01	<10	15	67	<10	58	3	
8V3613SG/SJ	5025E 2600N	435025	6222600	1024	<0.2	1.94	317	78	<0.5	<5	0.10	8	37	<1	60	7	2.01	<1	0.14	17	0.34	>10000	2	<0.01	<1	5509	760	0.09	18	2	8	<5	0.02	<10	<10	169	<10	162	6
8V3613SG/SJ	5025E 2625N	435025	6222625	52	<0.2	2.04	59	42	<0.5	<5	0.54	1	11	31	11	7.13	<1	0.05	<10	0.41	482	3	<0.01	6	784	56	0.05	15	2	14	<5	0.19	<10	<10	191	<10	51	8	
8V3613SG/SJ	5025E 2650N	435025	6222650	14	<0.2	2.36	64	61	<0.5	<5	0.24	1	15	2	28	10.10	<1	0.08	12	0.23	2807	<2	<0.01	<1	2618	64	0.05	17	1	7	<5	0.02	<10	<10	251	<10	62	8	
8V3613SG/SJ	5025E 2675N	435025	6222675	22	<0.2	2.01	23	35	<0.5	<5	0.09	<1	7	24	11	3.81	<1	0.05	<10	0.39	391	2	<0.01	5	932	45	0.06	9	1	13	<5	0.11	<10	<10	118	<10	41	4	
8V3613SG/SJ	5025E 2700N	435025	6222700	74	<0.2	2.07	58	117	<0.5	<5	0.05	1	10	<1	20	4.00	<1	0.11	16	0.29	2328	<2	<0.01	<1	2866	51	0.03	9	2	7	<5	0.01	<10	<10	128	<10	55	3	
8V3613SG/SJ	5025E 2725N	435025	6222725	10	<0.2	2.11	45	55	<0.5	<5	0.06	<1	10	<10	13	8.02	<1	0.05	<10	0.47	427	2	<0.01	7	842	43	0.04	16	2	12	<5	0.17	<10	<10	212	<10	53	12	
8V3613SG/SJ	5025E 2750N	435025	6222750	69	<0.2	3.21	105	79	<0.5	<5	0.05	2	15	69	34	7.26	<1	0.06	<10	0.73	628	3	<0.01	31	878	58	0.07	17	7	9	<5	0.09	<10	<10	205	<10	100	15	
8V3613SG/SJ	5025E 2775N	435025	6222775	36	<0.2	3.69	63	75	<0.5	<5	0.32	2	14	3	34	6.75	<1	0.07	<10	0.25	2168	2	<0.01	<1	1594	106	0.10	14	2	7	<5	0.06	<10	<10	164	<10	58	5	
8V3613SG/SJ	5025E 2800N	435025	6222800	48	<0.2	2.26	198	60	<0.5	<5	0.02	5	22	32	41	8.17	<1	0.07	14	0.38	1951	4	<0.01	12	1148	114	0.06	17	2	6	<5	0.13	<10	<10	175	<10	93	9	
8V3613SG/SJ	5050E 2550N	435050	6222550	66	<0.2	2.05	122	51	<0.5	<5	0.04	1	19	62	43	9.50	<1	0.06	15	0.25	909	4	0.01	4	1219	56	0.04	20	8	6	<5	0.15	<10	<10	306	<10	105	12	
8V3613SG/SJ	5050E 2575N	435050	6222575	36	<0.2	1.18	47	28	<0.5	<5	0.02	<1	8	20	9	4.82	<1	0.07	17	0.11	282	4	<0.01	1	908	41	0.05	9	1	5	<5	0.17	<10	<10	129	<10	61	15	
8V3613SG/SJ	5050E 2600N	435050	6222600	82	<0.2	1.61	99	144	<0.5	<5	0.15	2	40	<1	54	7.77	<1	0.12	<10	0.58	4154	2	0.02	1	4383	97	0.10	14	6	8	<5	0.01	<10	<10	244	<10	159	6	
8V3613SG/SJ	5050E 2625N	435050	6222625	208	<0.2	0.79	162	97	<0.5	<5	0.09	3	34	<1	39	6.69	<1	0.12	<10	0.20	7159	<2	<0.01	<1	4305	64	0.06	13	3	5	<5	0.01	<10	<10	173	<10	81	5	
8V3613SG/SJ	5050E 2650N	435050	6222650	144	<0.2	1.38	221	73	<0.5	<5	0.03	4	10	<1	6	6.84	<1	0.09	11	0.11	1509	2	0.04	<1	1248	96	0.04	12	1	4	<5	0.02	<10	<10	155	<10	96	5	
8V3613SG/SJ	5050E 2675N	435050	6222675	16	<0.2	1.43	42	42	<0.5	<5	0.05	<1	6	25	6	4.55	<1	0.05	11	0.14	185	2	<0.01	<1	1249	38	0.03	9	2	9	<5	0.11	<10	<10	206	<10	27	4	
8V3613SG/SJ	5050E 2700N	435050	6222700	88	<0.2	3.03	493	98	<0.5	<5	0.01	9	31	<1	61	9.83	<1	0.09	14	0.38	3069	<2	<0.01	<1	2473	93	0.08	21	4	4	<5	0.01	<10	<10	262	<10	86	8	
8V3613SG/SJ	5050E 2725N	435050	6222725	220	<0.2	1.92	131	57	<0.5	<5	0.05	2	7	25	27	4.54	<1	0.10	11	0.42	611	2	<0.01	4	2019	115	0.08	10	1	6	<5	0.01	<10	<10	117	<10	75	4	
8V3613SG/SJ	5050E 2750N	435050	6222750	16	<0.2	2.51	83	149	<0.5	<5	0.10	1	11	9	27	9.20	<1	0.09	<10	0.31	751	<2	<0.01	<1	1589	75	0.08	17	3	10	<5	0.06	<10	<10	313	<10	49	6	
8V3613SG/SJ	5050E 2775N	435050	6222775	48	<0.2	2.70	220	82	<0.5	<5	0.03	4	12	<1	22	8.67	<1	0.10	11	0.48	2031	<2	<0.01	<1	2805	64	0.07	17	3	6	<5	0.03	<10	<10	248	<10	80	7	
8V3613SG/SJ	5050E 2800N	435050	6222800	128	<0.2	1.05	199	105	<0.5	<5	0.02	4	14	<1	16	3.51	<1	0.08	13	0.09	3306	<2	<0.01	<1	1188	138	0.04	7	<1	5	<5	0.05	<10	<10	137	<10	64	2	
8V3613SG/SJ	5075E 2300N	435075	6222300	44	<0.2	3.56	147	56	<0.5	<5	0.05	2	14	<1	25	6.51	<1	0.07	11	0.36	1188	<2	<0.01	<1	1031	48	0.09	18	2	4	<5	0.15	<10	<10	173	<10	59	5	
8V3613SG/SJ	5075E 2325N	435075	6222325	342	<0.2	1.83	258	68	<0.5	<5	0.11	5	24	<1	22	8.78	<1	0.10	<10	0.21	2391	2	<0.01	<1	2528	134	0.10	18	1	7	<5	0.18	<10	<10	302	<10	54	6	
8V3613SG/SJ	5075E 2350N	435075	6222350	12	<0.2	1.38	69	44	<0.5	<5	0.08	1	23	26	6	5.71	<1	0.06	10	0.18	1734	9	<0.01	2	915	49	0.07	12	2	8	<5	0.24	<10	<10	283	<10	34	8	
8V3613SG/SJ	5075E 2375N	435075	6222375	360	<0.2	1.71	176	97	<0.5	<5	0.07	3	14	<1	17	6.53	<1	0.12	<10	0.20	2241	2	<0.01	<1	1074	155	0.09	12	1	6	<5	0.08	<10	<10	244	<10	53	4	
8V3613SG/SJ	5075E 2400N	435075	6222400	92	<0.2	1.74	121	366	<0.5	<5	0.64	3	17	<1	12	4.22	<1	0.10	10	0.36	5562	2	0.02	11	2059	212	0.11	9	<1	23	<5	0.02	<10	<10	139	<10	112	3	
8V3613SG/SJ	5075E 2425N	435075	6222425	44	<0.2	1.41	72	53	<0.5	<5	0.09	1	15	<1	15	3.79	<1	0.12	<10	0.45	2227	2	0.01	<1	1133	75	0.07	6	1	5	<5	0.01	<10	<10	99	<10	96	3	
8V3613SG/SJ	5075E 2450N	435075	6222450	10	<0.2	2.19	138	81	<0.5	<5	0.09	3	17	53	18	5.74	<1	0.13																					

DILWORTH PROPERTY SOIL SAMPLING ASSAY DATA - 2008

Certificate Number	Sample Number	Easting	Northing	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm	
8V3613SG/SJ	5125E 2450N	435125	6222450	14	<0.2	1.75	71	61	<0.5	<5	0.05	1	10	36	14	6.22	<1	0.05	<10	0.17	605	3	<0.01	2	890	46	0.07	13	2	7	<5	0.12	<10	<10	251	<10	65	5	
8V3613SG/SJ	5125E 2475N	435125	6222475	236	<0.2	1.69	929	69	<0.5	<5	0.05	19	11	51	20	7.16	<1	0.05	11	0.26	930	<2	0.01	4	1044	67	0.06	17	2	7	<5	0.09	<10	<10	246	<10	95	5	
8V3613SG/SJ	5125E 2500N	435125	6222500	230	1.3	1.08	449	70	<0.5	<5	0.03	9	8	<1	14	4.29	<1	0.08	<10	0.13	1104	<2	<0.01	<1	1342	51	0.05	9	1	4	<5	0.02	<10	<10	154	<10	29	3	
8V3613SG/SJ	5125E 2525N	435125	6222525	126	<0.2	1.28	73	51	<0.5	<5	0.04	1	9	43	10	4.31	<1	0.04	<10	0.48	750	2	<0.01	11	997	44	0.05	8	2	4	<5	0.01	<10	<10	117	<10	71	4	
8V3613SG/SJ	5125E 2550N	435125	6222550	15	<0.2	0.64	20	15	<0.5	<5	0.01	<1	3	6	5	1.02	<1	0.05	<10	0.02	81	<2	<0.01	1	400	13	0.02	<5	1	2	<5	0.01	<10	13	37	<10	29	2	
8V3613SG/SJ	5125E 2575N	435125	6222575	216	<0.2	1.52	931	73	<0.5	<5	0.03	19	12	22	25	7.10	<1	0.08	<10	0.14	484	2	<0.01	<1	1046	78	0.05	16	2	5	<5	0.01	<10	<10	223	<10	64	5	
8V3613SG/SJ	5125E 2600N	435125	6222600	74	<0.2	1.44	123	77	<0.5	<5	0.13	2	5	8	15	5.20	<1	0.06	<10	0.21	389	16	<0.01	<1	1415	41	0.08	12	1	6	<5	0.01	<10	<10	163	<10	60	5	
8V3613SG/SJ	5125E 2625N N.S.	435125	6222625																																				
8V3613SG/SJ	5125E 2650N	435125	6222650	393	<0.2	0.99	760	275	<0.5	<5	0.05	20	14	<1	11	7.90	<1	0.08	<10	0.07	6792	9	<0.01	<1	1035	97	0.36	19	3	4	<5	<0.01	<10	<10	120	<10	61	6	
8V3613SG/SJ	5125E 2675N	435125	6222675	636	<0.2	2.29	640	68	<0.5	<5	0.04	17	18	<1	43	6.01	<1	0.15	14	0.34	3073	5	<0.01	<1	3907	173	0.06	14	4	4	<5	0.01	<10	14	139	<10	101	10	
8V3613SG/SJ	5125E 2700N	435125	6222700	16	<0.2	1.28	41	43	<0.5	<5	0.04	1	6	19	9	4.08	<1	0.06	11	0.12	431	2	<0.01	2	938	64	0.04	9	1	7	<5	0.09	<10	<10	132	<10	57	4	
8V3613SG/SJ	5125E 2725N	435125	6222725	1418	90.3	1.00	1327	92	<0.5	<5	0.07	36	11	10	84	6.96	<1	0.08	<10	0.13	260	12	<0.01	1	3514	2192	0.16	33	2	9	<5	0.03	<10	<10	216	<10	383	5	
8V3613SG/SJ	5125E 2750N	435125	6222750	82	<0.2	2.37	53	70	<0.5	<5	0.03	1	5	9	16	4.92	<1	0.06	11	0.11	641	2	<0.01	<1	2593	54	0.06	10	1	6	<5	0.02	<10	<10	152	<10	31	5	
8V3613SG/SJ	5125E 2775N	435125	6222775	68	<0.2	2.70	55	107	<0.5	<5	0.06	1	5	14	13	6.62	<1	0.05	<10	0.18	531	2	<0.01	<1	1294	69	0.08	13	1	8	<5	0.05	<10	<10	151	<10	34	5	
8V3613SG/SJ	5125E 2800N	435125	6222800	44	<0.2	1.76	58	133	<0.5	<5	0.05	1	7	8	25	4.87	<1	0.05	<10	0.17	172	<2	<0.01	<1	1078	40	0.05	11	3	12	<5	0.04	<10	<10	240	<10	27	4	
8V3613SG/SJ	5150E 2300N	435150	6222300	8	<0.2	2.15	35	62	<0.5	<5	0.05	1	7	10	13	2.90	<1	0.08	<10	0.32	743	<2	<0.01	1	1225	34	0.07	7	1	6	<5	0.04	<10	<10	100	<10	39	2	
8V3613SG/SJ	5150E 2325N	435150	6222325	16	<0.2	2.29	65	46	<0.5	<5	0.19	1	9	33	15	3.55	<1	0.07	13	0.56	351	3	<0.01	13	1387	60	0.08	9	1	11	<5	0.10	<10	19	97	<10	89	7	
8V3613SG/SJ	5150E 2350N	435150	6222350	44	<0.2	3.04	803	99	<0.5	<5	0.35	22	28	24	45	5.82	<1	0.07	15	0.80	2279	2	<0.01	23	1954	82	0.06	14	3	21	<5	0.09	<10	32	135	<10	276	7	
8V3613SG/SJ	5150E 2375N	435150	6222375	48	<0.2	3.77	208	42	<0.5	<5	0.06	6	18	16	26	3.74	<1	0.05	25	0.19	1224	2	0.03	1	2227	104	0.15	10	1	5	<5	0.04	<10	64	79	<10	99	5	
8V3613SG/SJ	5150E 2400N	435150	6222400	26	<0.2	1.78	73	76	<0.5	<5	0.13	2	7	3	11	1.65	<1	0.08	10	0.13	417	2	<0.01	<1	780	33	0.04	6	1	5	<5	0.01	<10	<10	82	<10	23	2	
8V3613SG/SJ	5150E 2425N	435150	6222425	48	<0.2	3.84	224	90	<0.5	<5	0.32	6	60	<1	57	7.12	<1	0.16	14	0.87	6421	4	0.03	<1	2512	168	0.10	18	3	13	<5	0.10	<10	176	<10	204	7		
8V3613SG/SJ	5150E 2450N	435150	6222450	148	<0.2	3.91	524	91	<0.5	<5	0.20	14	65	<1	158	9.17	<1	0.15	18	0.77	4817	6	<0.01	3	3068	341	0.08	21	7	10	<5	0.11	<10	28	220	<10	355	16	
8V3613SG/SJ	5150E 2475N	435150	6222475	478	0.3	1.97	365	78	<0.5	<5	0.12	10	23	<1	54	5.72	<1	0.13	21	0.40	3873	<2	<0.01	<1	2256	196	0.09	13	4	6	<5	0.01	<10	126	<10	154	8		
8V3613SG/SJ	5150E 2500N	435150	6222500	66	<0.2	3.53	240	65	<0.5	<5	0.04	6	55	<1	37	9.42	<1	0.10	12	0.43	6365	<2	<0.01	<1	2274	224	0.09	22	2	6	<5	0.05	<10	208	<10	160	8		
8V3613SG/SJ	5150E 2525N	435150	6222525	14	<0.2	0.89	67	43	<0.5	<5	0.06	2	12	20	16	2.25	<1	0.06	<10	0.44	481	<2	<0.01	9	1327	49	0.07	9	2	5	<5	0.01	<10	<10	83	<10	87	4	
8V3613SG/SJ	5150E 2550N	435150	6222550	14	<0.2	1.17	49	92	<0.5	<5	0.30	1	17	24	20	4.61	<1	0.05	13	0.71	947	<2	<0.01	19	1523	42	0.05	9	4	12	<5	0.01	<10	13	89	<10	119	4	
8V3613SG/SJ	5150E 2575N N.S.	435150	6222575																																				
8V3613SG/SJ	5150E 2600N N.S.	435150	6222600																																				
8V3613SG/SJ	5150E 2625N	435150	6222625	312	3.2	1.55	515	73	<0.5	<5	0.14	13	18	10	79	6.41	<1	0.11	16	0.59	1673	3	<0.01	1	2107	215	0.09	17	3	8	<5	0.02	<10	18	132	<10	136	6	
8V3613SG/SJ	5150E 2650N	435150	6222650	1275	<0.2	0.58	4046	398	0.6	<5	0.11	110	15	<1	56	9.04	<1	0.12	<10	0.07	5158	2	<0.01	<1	1504	505	0.21	38	2	9	<5	<0.01	<10	<10	128	<10	139	7	
8V3613SG/SJ	5150E 2675N	435150	6222675	214	<0.2	1.17	59	46	<0.5	<5	0.03	1	3	6	7	2.04	<1	0.09	11	0.06	493	3	<0.01	<1	895	45	0.06	5	1	4	<5	0.05	<10	14	58	<10	27	4	
8V3613SG/SJ	5150E 2700N	435150	6222700	38	<0.2	1.81	37	33	<0.5	<5	0.07	<1	11	34	9	5.98	<1	0.04	<10	0.42	472	2	<0.01	7	593	63	0.04	13	2	12	<5	0.18	<10	1173	<10	63	9		
8V3613SG/SJ	5150E 2725N	435150	6222725	68	<0.2	2.31	48	53	<0.5	<5	0.26	1	12	42	20	5.49	<1	0.04	<10	0.79	483	<2	<0.01	17	1273	95	0.03	12	4	16	<5	0.13	<10	<10	145	<10	113	6	
8V3613SG/SJ	5150E 2750N	435150	6222750	592	<0.2	1.89	560	78	<0.5	<5	0.03	15	20	<1	30	5.64	<1	0.12	11	0.24	5716	2	<0.01	<1	2179	102	0.06	15	1	6	<5	0.02	<10	<10	123	<10	56	5	
8V3613SG/SJ	5150E 2775N	435150	6222775	214	<0.2	1.19	65	76	<0.5	<5	0.02	1	5	17	11	3.12	<1	0.07	11	0.17	537	2	<0.01	2	1322	40	0.03	7	1	5	<5	0.01	<10	10	74	<10	32	3	
8V3613SG/SJ	5150E 2800N	435150	6222800	94	<0.2	1.43	107	58	<0.5	<5	0.06	2	7	13	15	4.84	<1	0.05	10	0.18	381	4	<0.01	<1	975	43	0.02	12	2	12	<5	0.06	<10	<10	150	<10	56	4	
8V3613SG/SJ	5175E 2300N	435175	6222300	52	<0.2	1.86	434	126	<0.5	<5	0.56	12	10	28	11	4.62	<1	0.05	<10	0.39	500	2	<0.01	7	1212	62	0.10												

DILWORTH PROPERTY SOIL SAMPLING ASSAY DATA - 2008

Certificate Number	Sample Number	Easting	Northing	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3613SG/SJ	5200E 2650N	435200	6222650	524	10.7	1.84	1818	84	0.5	<5	0.05	44	59	<1	89	9.94	<1	0.16	17	0.77	4071	4	<0.01	<1	4125	262	0.07	31	6	5	<5	0.01	<10	16	193	<10	220	9
8V3613SG/SJ	5200E 2675N	435200	6222675	50	<0.2	1.60	239	98	<0.5	<5	0.03	6	10	4	23	6.92	<1	0.08	16	0.11	1247	<2	<0.01	<1	1126	114	0.04	13	2	5	<5	0.02	<10	13	155	<10	131	5
8V3613SG/SJ	5200E 2700N	435200	6222700	1410	0.9	1.19	309	57	<0.5	<5	0.07	6	17	<1	146	6.10	<1	0.11	16	0.12	3706	<2	<0.01	<1	2327	3057	0.05	18	2	4	<5	0.01	<10	13	126	<10	545	5
8V3613SG/SJ	5200E 2725N	435200	6222725	208	<0.2	0.69	769	53	<0.5	<5	0.02	15	31	<1	36	7.46	<1	0.14	18	0.11	4023	<2	<0.01	<1	3818	125	0.05	21	1	4	<5	0.01	<10	12	142	<10	74	5
8V3613SG/SJ	5200E 2750N	435200	6222750	62	<0.2	2.46	88	82	<0.5	6	0.09	2	16	6	19	6.86	<1	0.07	10	0.32	3132	4	<0.01	<1	2820	122	0.12	16	1	9	<5	0.10	<10	221	<10	85	6	
8V3613SG/SJ	5200E 2775N	435200	6222775	784	20.4	1.54	574	75	<0.5	<5	0.05	12	14	<1	22	6.54	<1	0.05	10	0.26	2552	3	<0.01	<1	2171	167	0.05	19	1	6	<5	0.01	<10	156	<10	104	4	
8V3613SG/SJ	5200E 2800N	435200	6222800	402	<0.2	1.17	122	112	<0.5	<5	0.25	2	18	55	27	5.39	<1	0.06	12	0.83	1095	<2	<0.01	21	1494	67	0.06	13	2	9	<5	0.02	<10	137	<10	130	4	
8V3613SG/SJ	5225E 2300N	435225	6222300	55	<0.2	2.42	29	55	<0.5	<5	0.12	<1	15	79	17	6.90	<1	0.04	<10	0.85	711	<2	0.02	15	789	41	0.06	15	3	14	<5	0.18	<10	217	<10	88	12	
8V3613SG/SJ	5225E 2325N	435225	6222325	284	<0.2	1.99	684	70	<0.5	<5	0.03	14	22	<1	16	6.71	<1	0.09	<10	1.13	3271	<2	<0.01	<1	3273	80	0.12	14	<1	5	<5	0.01	<10	201	<10	39	5	
8V3613SG/SJ	5225E 2350N	435225	6222350	2	<0.2	2.59	25	43	<0.5	<5	0.06	<1	7	48	12	9.05	<1	0.05	19	0.21	425	4	0.03	<1	942	48	0.10	18	1	7	<5	0.17	<10	59	196	<10	55	64
8V3613SG/SJ	5225E 2375N	435225	6222375	12	<0.2	0.82	14	22	<0.5	<5	0.03	<1	2	11	3	0.74	<1	0.05	<10	0.04	87	2	<0.01	1	687	48	0.05	<5	<1	4	<5	0.06	<10	37	<10	12	1	
8V3613SG/SJ	5225E 2400N	435225	6222400	852	<0.2	2.28	5411	85	<0.5	<5	0.05	114	82	<1	66	11.95	<1	0.15	12	0.49	9123	4	<0.01	<1	6741	306	0.09	49	2	6	<5	0.05	<10	317	<10	151	10	
8V3613SG/SJ	5225E 2425N	435225	6222425	12	<0.2	1.57	47	46	<0.5	<5	0.09	<1	12	66	12	5.16	<1	0.03	<10	0.60	565	<2	0.02	13	1099	34	0.06	11	2	12	<5	0.13	<10	183	<10	61	5	
8V3613SG/SJ	5225E 2450N	435225	6222450	48	<0.2	2.26	33	61	<0.5	<5	0.35	<1	15	69	20	4.83	<1	0.04	10	0.76	745	<2	0.01	20	1119	37	0.04	11	3	17	<5	0.11	<10	155	<10	98	5	
8V3613SG/SJ	5225E 2475N	435225	6222475	60	<0.2	1.72	464	63	<0.5	<5	0.10	9	7	27	18	4.77	<1	0.04	13	0.14	819	3	<0.01	<1	1333	57	0.07	11	1	12	<5	0.06	<10	100	144	<10	49	5
8V3613SG/SJ	5225E 2500N	435225	6222500	206	<0.2	2.60	676	93	<0.5	<5	0.03	14	21	<1	22	10.15	<1	0.08	10	0.22	3993	9	0.02	<1	1329	215	0.09	23	1	4	<5	0.02	<10	13	218	<10	78	18
8V3613SG/SJ	5225E 2525N	435225	6222525	2253	2.8	2.42	4113	103	1.7	<5	0.20	87	46	<1	86	10.80	<1	0.10	26	0.40	6023	2	<0.01	<1	3886	339	0.12	48	5	9	<5	0.01	<10	47	226	<10	233	14
8V3613SG/SJ	5225E 2550N	435225	6222550	171	0.8	2.48	1044	111	<0.5	<5	0.07	22	17	12	33	7.93	<1	0.07	10	0.25	1480	<2	<0.01	<1	2221	329	0.10	21	1	6	<5	0.01	<10	250	<10	176	6	
8V3613SG/SJ	5225E 2575N	435225	6222575	122	<0.2	2.37	2117	162	<0.5	<5	0.05	44	17	<1	29	9.80	<1	0.09	15	0.22	2561	<2	<0.01	<1	2082	202	0.04	28	2	4	<5	0.01	<10	270	<10	114	7	
8V3613SG/SJ	5225E 2600N	435225	6222600	560	<0.2	2.58	1819	84	<0.5	<5	0.04	39	34	<1	41	9.59	<1	0.09	14	0.49	5604	4	<0.01	<1	2603	515	0.07	27	6	6	<5	0.02	<10	20	251	<10	326	11
8V3613SG/SJ	5225E 2625N	435225	6222625	495	<0.2	1.99	1359	104	0.5	<5	0.34	30	48	<1	88	8.18	<1	0.13	15	0.82	5512	4	<0.01	<1	2517	344	0.09	25	4	10	<5	0.01	<10	212	<10	218	8	
8V3613SG/SJ	5225E 2650N	435225	6222650	1203	17.4	2.00	2990	94	0.8	<5	0.01	59	73	<1	124	9.56	<1	0.12	21	0.53	7318	4	<0.01	<1	2744	365	0.06	38	8	4	<5	0.01	<10	15	229	<10	261	9
8V3613SG/SJ	5225E 2675N	435225	6222675	1011	<0.2	2.36	560	84	<0.5	<5	0.08	11	29	<1	43	10.75	<1	0.09	14	0.36	3492	2	<0.01	<1	5269	522	0.08	26	3	8	<5	0.05	<10	248	<10	265	8	
8V3613SG/SJ	5225E 2700N	435225	6222700	59	<0.2	1.10	230	58	<0.5	<5	0.06	4	13	<1	13	6.76	<1	0.09	14	0.16	1827	2	<0.01	<1	2213	98	0.06	13	1	6	<5	0.07	<10	184	<10	87	5	
8V3613SG/SJ	5225E 2725N	435225	6222725	74	<0.2	1.08	257	79	<0.5	<5	0.01	7	9	<1	17	4.92	<1	0.13	19	0.07	1486	<2	<0.01	<1	3444	102	0.05	11	1	4	<5	<0.01	<10	28	74	<10	48	6
8V3613SG/SJ	5225E 2750N	435225	6222750	105	<0.2	0.95	208	56	<0.5	<5	0.11	5	19	<1	21	5.55	<1	0.09	12	0.10	2730	2	<0.01	<1	2165	127	0.06	12	1	12	<5	0.08	<10	153	<10	57	4	
8V3613SG/SJ	5225E 2775N	435225	6222775	69	<0.2	1.48	765	45	<0.5	<5	0.10	20	15	14	15	7.67	<1	0.08	<10	0.38	2639	<2	<0.01	3	3267	86	0.07	21	2	16	<5	0.16	<10	203	<10	59	6	
8V3613SG/SJ	5225E 2800N	435225	6222800	242	<0.2	0.86	452	226	<0.5	<5	0.49	12	13	11	24	5.57	<1	0.12	<10	0.31	1250	5	<0.01	<1	2095	68	0.10	15	1	24	<5	<0.01	<10	103	<10	125	4	
8V3613SG/SJ	5250E 2300N	435250	6222300	12	<0.2	1.57	91	92	<0.5	<5	0.04	2	24	<1	31	7.82	<1	0.11	<10	0.17	2263	2	<0.01	<1	1850	49	0.09	15	3	5	<5	<0.01	<10	137	<10	147	7	
8V3613SG/SJ	5250E 2325N	435250	6222325	47	<0.2	2.38	1025	62	<0.5	<5	0.07	27	36	7	44	9.30	<1	0.12	15	0.47	6278	4	0.03	<1	4420	137	0.12	25	3	8	<5	0.19	<10	20	250	<10	172	12
8V3613SG/SJ	5250E 2350N	435250	6222350	<1	<0.2	2.23	23	49	<0.5	<5	0.12	<1	10	33	10	4.97	<1	0.04	10	0.47	557	2	<0.01	12	805	36	0.05	11	3	17	<5	0.15	<10	159	<10	55	6	
8V3613SG/SJ	5250E 2375N	435250	6222375	12	<0.2	2.33	15	51	<0.5	<5	0.13	<1	7	31	4	3.85	<1	0.05	<10	0.36	436	<2	<0.01	6	570	41	0.04	9	2	19	<5	0.14						

DILWORTH PROPERTY SOIL SAMPLING ASSAY DATA - 2008

Certificate Number	Sample Number	Easting	Northing	Au ppb	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
8V3613SG/SJ	5300E 2325N	435300	6222325	84	1.7	1.00	142	63	<0.5	<5	0.03	4	6	8	22	2.36	<1	0.08	<10	0.09	599	<2	0.01	<1	979	37	0.06	6	<1	4	<5	0.01	<10	<10	99	<10	21	2
8V3613SG/SJ	5300E 2350N	435300	6222350	19	<0.2	1.69	44	21	<0.5	<5	0.10	1	5	20	17	3.81	<1	0.06	17	0.15	399	10	0.09	2	1356	42	0.12	9	<1	5	<5	0.10	<10	70	71	<10	65	39
8V3613SG/SJ	5300E 2375N	435300	6222375	24	<0.2	1.19	19	26	<0.5	<5	0.06	<1	5	23	5	2.09	<1	0.05	10	0.25	159	4	<0.01	5	989	39	0.07	5	1	5	<5	0.10	<10	36	62	<10	37	14
8V3613SG/SJ	5300E 2400N	435300	6222400	29	<0.2	1.44	35	63	<0.5	<5	0.23	<1	15	38	29	4.03	<1	0.05	<10	0.82	987	<2	0.03	27	1303	40	0.01	9	4	13	<5	0.08	<10	13	114	<10	104	4
8V3613SG/SJ	5300E 2425N	435300	6222425	6	<0.2	1.48	19	31	<0.5	<5	0.07	<1	5	33	6	3.86	<1	0.02	<10	0.27	236	<2	0.04	4	566	28	0.03	8	2	9	<5	0.11	<10	16	120	<10	34	6
8V3613SG/SJ	5300E 2450N	435300	6222450	20	<0.2	2.14	31	48	<0.5	<5	0.10	<1	8	40	13	6.02	<1	0.02	<10	0.42	466	<2	0.03	12	828	50	0.06	13	2	12	<5	0.11	<10	<10	149	<10	52	7
8V3613SG/SJ	5300E 2475N	435300	6222475	12	<0.2	1.44	33	32	<0.5	<5	0.05	<1	9	32	7	6.24	<1	0.03	<10	0.33	750	<2	0.03	7	1580	38	0.05	13	2	9	<5	0.16	<10	12	164	<10	45	9
8V3613SG/SJ	5300E 2500N	435300	6222500	19	<0.2	1.61	32	37	<0.5	<5	0.07	<1	10	36	13	5.55	<1	0.03	<10	0.56	733	<2	0.02	13	1324	36	0.04	11	2	11	<5	0.11	<10	<10	151	<10	62	5
8V3613SG/SJ	5300E 2525N	435300	6222525	756	<0.2	1.04	817	161	<0.5	<5	0.03	21	61	<1	105	10.96	<1	0.14	10	0.45	5209	<2	0.03	<1	3845	210	0.16	31	4	9	<5	0.01	<10	17	204	<10	115	11
8V3613SG/SJ	5300E 2550N	435300	6222550	546	29.7	1.33	1030	135	<0.5	<5	0.20	30	39	2	206	10.80	<1	0.19	13	0.50	2902	3	0.03	<1	3256	648	0.36	44	7	16	<5	0.03	<10	19	227	10	706	10
8V3613SG/SJ	5300E 2575N	435300	6222575	64	44.2	1.66	73	25	<0.5	<5	0.04	2	3	7	31	1.18	<1	0.05	<10	0.05	66	<2	0.02	2	2768	28	0.15	5	<1	3	<5	0.01	<10	<10	24	<10	18	2
8V3613SG/SJ	5300E 2600N	435300	6222600	47	<0.2	1.81	239	34	<0.5	<5	0.05	6	7	34	23	6.08	<1	0.06	26	0.53	499	2	0.05	6	1564	70	0.09	12	2	5	<5	0.07	<10	46	132	<10	65	9
8V3613SG/SJ	5300E 2625N	435300	6222625	298	<0.2	0.71	745	61	<0.5	<5	0.02	20	4	9	21	5.84	<1	0.07	<10	0.10	272	<2	<0.01	<1	1719	42	0.07	16	1	5	<5	0.02	<10	<10	146	<10	30	4
8V3613SG/SJ	5300E 2650N	435300	6222650	8	<0.2	2.18	264	52	<0.5	<5	0.04	6	40	<1	26	8.84	<1	0.06	<10	0.28	>10000	3	<0.01	<1	2317	83	0.10	18	1	6	<5	0.06	<10	<10	235	<10	45	6
8V3613SG/SJ	5300E 2675N	435300	6222675	64	<0.2	1.95	907	51	<0.5	<5	0.05	24	28	11	40	8.68	<1	0.06	12	0.64	2750	5	0.04	<1	2425	90	0.09	25	2	8	<5	0.03	<10	12	197	<10	90	6
8V3613SG/SJ	5300E 2700N	435300	6222700	1710	<0.2	1.62	19	54	<0.5	<5	0.24	<1	12	31	15	3.78	<1	0.03	<10	0.70	577	<2	0.03	20	786	29	0.02	8	3	15	<5	0.10	<10	<10	105	<10	77	3
8V3613SG/SJ	5300E 2725N	435300	6222725	<1	34.2	1.08	6282	72	<0.5	5	0.05	177	33	3	101	11.92	<1	0.08	14	0.37	3504	<2	0.03	<1	2477	433	0.14	79	4	7	<5	0.02	<10	22	221	<10	208	10
8V3613SG/SJ	5300E 2750N	435300	6222750	528	4.0	1.03	2085	77	<0.5	<5	0.05	56	9	11	23	4.39	<1	0.09	10	0.20	1109	<2	0.02	<1	2121	123	0.03	25	1	4	<5	0.02	<10	17	87	<10	53	3
8V3613SG/SJ	5300E 2775N	435300	6222775	128	<0.2	1.34	159	97	0.7	<5	0.03	4	29	<1	62	5.73	<1	0.08	14	0.16	2804	4	0.02	<1	2145	78	0.04	13	4	4	<5	0.01	<10	39	102	<10	106	7
8V3613SG/SJ	5300E 2800N	435300	6222800	1161	5.0	1.05	993	338	0.8	<5	0.50	27	35	<1	98	7.43	<1	0.12	18	0.52	3310	2	<0.01	6	2120	186	0.23	23	4	22	<5	0.02	<10	20	129	<10	443	7

Dilworth Stream Sediment Samples Analytical - 2008

Certificate Number	Sample Number	Easting	Northing	Au ppb	Ag ppm	As ppm	Pb ppm	Zn ppm	Zr ppm
8V3008SG/SJ	SL01	437886	6222464	4	<0.2	17	15	120	4
8V3008SG/SJ	SL02	437879	6222812	1	<0.2	18	14	127	5
8V3008SG/SJ	SL03	437858	6222920	4	0.2	18	20	153	4
8V3008SG/SJ	SL04	437893	6222937	2	0.2	15	17	150	5
8V3008SG/SJ	SL05	437921	6222948	<1	<0.2	14	14	142	5
8V3008SG/SJ	SL06	437976	6223236	1	<0.2	9	10	113	3
8V3008SG/SJ	SL07	437901	6223472	2	<0.2	9	10	125	5
8V3008SG/SJ	SL08	437902	6223642	<1	<0.2	16	15	138	4
8V3008SG/SJ	SL09	438061	6223961	1	<0.2	10	10	123	4
8V3008SG/SJ	SL10	438057	6223992	<1	<0.2	9	9	112	5
8V3008SG/SJ	SL11	438128	6224148	8	<0.2	11	11	119	4
8V3008SG/SJ	SL12	438113	6224271	4	<0.2	10	10	113	5
8V3008SG/SJ	SL13	438064	6224401	3	<0.2	13	12	144	5
8V3008SG/SJ	SL14	438114	6224655	4	<0.2	14	12	146	6
8V3008SG/SJ	SL15	438182	6225027	2	<0.2	15	17	161	6
8V3008SG/SJ	SL16	438189	6225144	4	<0.2	15	19	139	9
8V3008SG/SJ	SL17	438213	6225288	7	<0.2	18	17	152	6
8V3008SG/SJ	SL18	438217	6225314	2	<0.2	12	12	133	4
8V3008SG/SJ	SL19	438341	6225605	<1	<0.2	17	15	166	5
8V3008SG/SJ	SL20	438390	6225726	24	<0.2	20	15	153	6
8V3008SG/SJ	SL21	438572	6225813	5	<0.2	21	15	219	7
8V3008SG/SJ	SL22	438570	6225841	27	<0.2	17	15	166	8
8V3008SG/SJ	SL23	438575	6226209	6	0.2	23	18	177	7
8V3008SG/SJ	SL24	438595	6226681	6	0.2	9	9	107	4
8V3008SG/SJ	SL25	438562	6226807	1	<0.2	9	13	110	6
8V3008SG/SJ	SL26	438458	6227042	12	0.3	30	21	201	6
8V3008SG/SJ	SL27	438441	6227414	7	0.2	23	15	248	6
8V3008SG/SJ	SL28	438436	6227429	4	<0.2	33	14	463	8
8V3008SG/SJ	SL29	438429	6227490	6	<0.2	35	12	284	6
8V3008SG/SJ	SL30	438379	6227726	4	<0.2	19	12	272	7
8V3008SG/SJ	SL31	438396	6227800	1	<0.2	20	12	223	7
8V3008SG/SJ	SL32	438178	6228233	5	0.3	25	13	206	8
8V3008SG/SJ	SL33	438083	6228521	16	0.3	38	21	398	9
8V3008SG/SJ	SL34	438233	6228669	7	<0.2	21	10	266	7
8V3008SG/SJ	SL35	438319	6228796	10	<0.2	20	11	213	5
8V3008SG/SJ	SL36	438171	6229278	31	0.5	37	25	300	7
8V3081SG/SJ	SL37	434663	6221917	15	0.5	78	46	194	4
8V3081SG/SJ	SL38	434698	6222030	57	0.4	140	75	235	5
8V3081SG/SJ	SL39	434860	6222478	8	0.2	30	19	86	4
8V3081SG/SJ	SL40	434844	6222634	110	4.6	98	69	114	3
8V3081SG/SJ	SL41	434856	6222905	202	2.2	101	60	193	4
8V3081SG/SJ	SL42	434824	6223018	165	1.4	248	153	842	5
8V3081SG/SJ	SL43	434767	6223129	70	3.0	168	91	336	4
8V3081SG/SJ	SL44	434732	6223252	218	3.2	422	449	546	5
8V3081SG/SJ	SL45	434646	6223720	1624	7.9	197	709	584	6
8V3081SG/SJ	SL46	434704	6223925	280	2.0	214	240	415	5
8V3081SG/SJ	SL47	434897	6224245	177	3.1	76	111	193	5
8V3081SG/SJ	SL48	434930	6224346	<1	<0.2	9	9	71	3
8V3081SG/SJ	SL49	434928	6224374	1	<0.2	9	8	75	3
8V3081SG/SJ	SL50	434866	6224661	1	<0.2	8	10	80	5
8V3081SG/SJ	SL51	434840	6224746	2	<0.2	21	11	90	4
8V3081SG/SJ	SL52	434812	6224833	19	<0.2	47	18	108	6

Dilworth Stream Sediment Samples Analytical - 2008

Certificate Number	Sample Number	Easting	Northing	Au ppb	Ag ppm	As ppm	Pb ppm	Zn ppm	Zr ppm
8V3081SG/SJ	SL53	434779	6224950	3	<0.2	205	19	102	7
8V3081SG/SJ	SL54	434786	6225111	23	0.3	85	40	143	5
8V3081SG/SJ	SL55	434774	6225164	4	<0.2	22	22	91	4
8V3100SG/SJ	SL56	434797	6225281	8	<0.2	15	22	127	3
8V3100SG/SJ	SL57	434793	6225311	5	<0.2	14	22	110	4
8V3100SG/SJ	SL58	434738	6225421	<1	<0.2	8	16	99	2
8V3100SG/SJ	SL59	434741	6225577	2	<0.2	9	21	128	4
8V3100SG/SJ	SL60	434735	6225681	3	<0.2	9	18	147	4
8V3100SG/SJ	SL61	434728	6225744	2	<0.2	10	19	120	3
8V3100SG/SJ	SL62	434703	6225825	8	<0.2	7	17	118	4
8V3100SG/SJ	SL63	434716	6225993	37	0.2	10	19	130	3
8V3100SG/SJ	SL64	434710	6226016	5	<0.2	7	18	146	4
8V3100SG/SJ	SL65	434637	6226279	9	0.4	48	42	118	3
8V3100SG/SJ	SL66	434895	6226722	4	<0.2	11	22	113	3
8V3100SG/SJ	SL67	434842	6226937	4	<0.2	13	29	158	3
8V3100SG/SJ	SL68	434953	6227047	4	<0.2	10	17	154	3
8V3100SG/SJ	SL69	435023	6227088	3	<0.2	17	21	237	4
8V3100SG/SJ	SL70	435114	6227213	4	<0.2	11	18	171	3
8V3100SG/SJ	SL71	435265	6227313	2	<0.2	9	14	134	3
8V3100SG/SJ	SL72	435287	6227382	3	0.2	<5	38	221	3
8V3100SG/SJ	SL73	435029	6227760	8	0.2	10	21	201	4
8V3100SG/SJ	SL74	434746	6228275	5	0.2	20	20	206	5
8V3100SG/SJ	SL75	434760	6228300	3	<0.2	<5	12	139	3

STANDARDS AND BLANKS

Certificate Number	Hole No.	Sample Number	Standard Number	WCM Values			Assayers Values			% Diff Assayers vs WCM		
				Au g/t	Ag g/t	Cu ppm	Au g/t	Ag g/t	Cu ppm	Au	Ag	Cu
BLANK												
8V2229RA/RJ	HL08-01	48719	Blank				0.19	2.7	51			
8V2229RA/RJ	HL08-01	48746	Blank				<0.01	<0.1	<1			
8V2278RA/RJ	HL08-01	48776	Blank				0.01	<0.2	1			
8V2278RA/RJ	HL08-01	48811	Blank				0.01	<0.2	<1			
8V2278RA/RJ	HL08-03	48860	Blank				0.02	<0.2	3			
8V2297RA/RJ	HL08-03	48935	Blank				0.01	<0.2	<1			
8V2297RA/RJ	HL08-03	48989	Blank				<0.01	0.2	11			
8V2297RA/RJ	HL08-04	83527	Blank				0.01	1.4	2			
8V2349RA/RJ	HL08-04	83599	Blank				<0.01	<0.2	2			
8V2349RA/RJ	HL08-05	83661	Blank				<0.01	<0.2	<1			
8V2376RA/RJ	HL08-06	83721	Blank				<0.01	4.1	1.0			
8V2415RA/RJ	HL08-08	83796	Blank				<0.01	0.3	<1			
8V2472RA/RJ	HL08-10	83955A	Blank				<0.01	<0.1	<1			
8V2472RA/RJ	HL08-10	83979A	Blank				0.01	<0.1	<1			
8V2472RA/RJ	HL08-11	84026	Blank				<0.01	<0.1	<1			
8V2472RA/RJ	HL08-11	84058A	Blank				<0.01	<0.1	<1			
8V2472RA/RJ	HL08-11	84085	Blank				0.01	<0.1	<1			
8V2508RA/RJ	HL08-12	84135	Blank				<0.01	<0.2	<1			
8V2508RA/RJ	HL08-12	84180	Blank				<0.01	0.2	3			
8V2508RA/RJ	HL08-12	84225	Blank				0.01	<0.2	<1			
8V2558RA/RJ	HL08-13	84300	Blank				0.03	<0.1	<1			
8V2558RA/RJ	HL08-14	84256	Blank				<0.01	<0.1	<1			
8V2558RA/RJ	HL08-15	84350	Blank				0.01	<0.1	<1			
8V2596RA/RJ	HL08-16	84400	Blank				<0.01	<0.1	2			
8V2690RA/RJ	HL08-16	84450	Blank				<0.01	<0.1	1			
8V2596RA/RJ	HL08-17	84500	Blank				<0.01	<0.1	6			
8V2690RA/RJ	HL08-17	84550	Blank				<0.01	<0.1	1			
8V2690RA/RJ	HL08-17	84575A	Blank				<0.01	<0.1	<1			
8V2690RA/RJ	HL08-18	84625	Blank				<0.01	<0.1	<1			
8V2690RA/RJ	HL08-18	84675	Blank				0.01	<0.1	<1			
8V2698RA/RJ	HL08-18	84725	Blank				0.01	1.6	4			
8V2690RA/RJ	HL08-19	84775	Blank				<0.01	<0.1	2			
8V2698RA/RJ	HL08-19	84825	Blank				<0.01	<0.1	2			
8V2698RA/RJ	HL08-20	84850	Blank				0.01	<0.1	<1			
8V2698RA/RJ	HL08-21	84900	Blank				<0.01	<0.1	<1			
8V2768RA/RJ	HL08-21	84950	Blank				0.01	<0.1	<1			
8V2768RA/RJ	HL08-22	85000	Blank				<0.01	<0.1	<1			
8V2768RA/RJ	HL08-23	85050	Blank				<0.01	<0.1	<1			
8V2768RA/RJ	HL08-23	85100	Blank				<0.01	<0.1	<1			
8V2768RA/RJ	HL08-23	85150	Blank				0.01	<0.1	10			
8V2699RA/RJ	HL08-24	85200	Blank				<0.01	<0.1	3			
8V2821RA/RJ	HL08-25	85250	Blank				<0.01	<0.1	<1			
8V2821RA/RJ	HL08-25	85300	Blank				<0.01	<0.1	<1			
8V2821RA/RJ	HL08-26	85350	Blank				<0.01	<0.1	1			
8V2820RA/RJ	HL08-28	85400	Blank				0.01	<0.1	<1			
8V2819RA/RJ	HL08-31	85450	Blank				<0.01	<0.1	<1			
8V2936RA/RJ	HL08-32	85500	Blank				0.01	<0.1	76			
8V3008RA/RJ	HL08-32	120050	Blank				<0.01	<0.1	<1			
8V3008RA/RJ	HL08-32	120100	Blank				<0.01	<0.1	<1			
8V3063RA/RJ	HL08-33	120150	Blank				<0.01	<0.1	<1			
8V3063RA/RJ	HL08-33	120200	Blank				0.01	<0.1	<1			
8V3063RA/RJ	HL08-34	120225	Blank				0.02	<0.1	4			
8V3081RA/RJ	HL08-35	120300	Blank				<0.01	<0.1	7			
8V3081RA/RJ	HL08-35	120350	Blank				0.01	<0.1	3			
8V3081RA/RJ	HL08-36	120375	Blank				<0.01	<0.1	2			
8V3100RA/RJ	HL08-36	120425	Blank				<0.01	<0.1	2			
8V3100RA/RJ	HL08-36	120475	Blank				<0.01	<0.1	<1			
8V3100RA/RJ	HL08-37	120500	Blank				<0.01	<0.1	<1			
8V3190RA/RJ	HL08-37	120550	Blank				0.01	<0.1	2			
8V3190RA/RJ	HL08-37	120600	Blank				<0.01	0.7	7			

STANDARDS AND BLANKS

Certificate Number	Hole No.	Sample Number	Standard Number	WCM Values			Assayers Values			% Diff Assayers vs WCM		
				Au g/t	Ag g/t	Cu ppm	Au g/t	Ag g/t	Cu ppm	Au	Ag	Cu
8V3190RA/RJ	HL08-38	120650	Blank	N/A			0.01	<0.1	4	N/A		
8V3215RA/RJ	HL08-38	120700	Blank	N/A			0.01	<0.1	<1	N/A		
8V3215RA/RJ	HL08-38	120750	Blank	N/A			0.01	<0.1	1	N/A		
8V3215RA/RJ	HL08-39	120800	Blank	N/A			<0.01	<0.1	<1	N/A		
8V3283RA/RJ	HL08-40	125850	Blank	N/A			0.01	<0.1	<1	N/A		
8V3283RA/RJ	HL08-40	125900	Blank	N/A			<0.01	<0.1	1	N/A		
8V3215RA/RJ	HL08-41	125950	Blank	N/A			<0.01	<0.1	3	N/A		
8V3283RA/RJ	HL08-42	120775	Blank	N/A			<0.01	<0.1	1	N/A		
8V3283RA/RJ	HL08-43	120850	Blank	N/A			0.01	<0.1	1	N/A		
8V3298RA/RJ	HL08-44	120875	Blank	N/A			0.01	<0.1	1	N/A		
8V3298RA/RJ	HL08-45	120950	Blank	N/A			0.01	<0.1	4	N/A		
8V3298RA/RJ	HL08-46	121000	Blank	N/A			<0.01	<0.1	2	N/A		
8V3298RA/RJ	HL08-46	121050	Blank	N/A			<0.01	<0.1	4	N/A		
8V3298RA/RJ	HL08-46	121100	Blank	N/A			0.01	<0.1	2	N/A		
8V3374RA/RJ	HL08-47	130050	Blank	N/A			0.01	<0.1	1	N/A		
8V3395RA/RJ	HL08-47	130100	Blank	N/A			<0.01	<0.1	<1	N/A		
8V3497RA/RJ	HL08-47	130150	Blank	N/A			0.01	<0.1	2	N/A		
8V3374RA/RJ	HL08-48	121125	Blank	N/A			<0.01	<0.1	1	N/A		
8V3374RA/RJ	HL08-48	121175	Blank	N/A			0.01	<0.1	<1	N/A		
8V3374RA/RJ	HL08-49	121225	Blank	N/A			<0.01	<0.1	1	N/A		
8V3374RA/RJ	HL08-50	121250	Blank	N/A			0.01	<0.1	<1	N/A		
8V3395RA/RJ	HL08-50	121300	Blank	N/A			0.01	<0.1	<1	N/A		
8V3395RA/RJ	HL08-51	121325	Blank	N/A			<0.01	<0.1	<1	N/A		
8V3395RA/RJ	HL08-53	121375	Blank	N/A			<0.01	<0.1	<1	N/A		
8V3497RA/RJ	HL08-53	121425	Blank	N/A			<0.01	<0.1	<1	N/A		
8V3497RA/RJ	HL08-53	121475	Blank	N/A			<0.01	<0.1	4	N/A		
8V3498RA/RJ	HL08-54	121550	Blank	N/A			<0.01	<0.1	2	N/A		
8V3498RA/RJ	HL08-54	121600	Blank	N/A			<0.01	<0.1	3	N/A		
8V3497RA/RJ	HL08-55	130200	Blank	N/A			0.01	<0.1	4	N/A		
8V3498RA/RJ	HL08-55	130250	Blank	N/A			<0.01	<0.1	1	N/A		
8V3551RA/RJ	HL08-55	130300	Blank	N/A			0.01	0.1	<1	N/A		
8V3551RA/RJ	HL08-55	130350	Blank	N/A			<0.01	2.4	2	N/A		
8V3551RA/RJ	HL08-55	130400	Blank	N/A			<0.01	<0.1	2	N/A		
8V3613RA/RJ	HL08-55	130450	Blank	N/A			0.01	2.8	<1	N/A		
8V3634RA/RJ	HL08-55	130500	Blank	N/A			<0.01	<0.1	2	N/A		
8V3551RA/RJ	HL08-56	121650	Blank	N/A			0.01	<0.1	1	N/A		
8V3551RA/RJ	HL08-56	121700	Blank	N/A			0.01	<0.1	<1	N/A		
8V3613RA/RJ	HL08-57	121750	Blank	N/A			<0.01	<0.1	3	N/A		
8V3613RA/RJ	HL08-57	121800	Blank	N/A			<0.01	<0.1	29	N/A		
8V3634RA/RJ	HL08-58	130525	Blank	N/A			<0.01	<0.1	1	N/A		
8V3634RA/RJ	HL08-58	130575	Blank	N/A			<0.01	<0.1	2	N/A		
8V3634RA/RJ	HL08-58	130625	Blank	N/A			<0.01	<0.1	3	N/A		
8V3634RA/RJ	HL08-58	130675	Blank	N/A			<0.01	<0.1	2	N/A		
8V3633RA/RJ	HL08-59	121875	Blank	N/A			0.01	4.1	11	N/A		
8V3633RA/RJ	HL08-59	121925	Blank	N/A			<0.01	3.0	2	N/A		
8V3671RA/RJ	HL08-59	121975	Blank	N/A			<0.01	<0.1	3	N/A		
8V3671RA/RJ	HL08-60	122000	Blank	N/A			<0.01	<0.1	4	N/A		
8V3671RA/RJ	HL08-60	122050	Blank	N/A			<0.01	<0.1	4	N/A		
8V3671RA/RJ	HL08-60	122100	Blank	N/A			<0.01	<0.1	7	N/A		
8V3699RA/RJ	HL08-61	122325	Blank	N/A			<0.01	<0.1	2	N/A		
8V3699RA/RJ	HL08-61	122350	Blank	N/A			<0.01	<0.1	1	N/A		
8V3699RA/RJ	HL08-61	122375	Blank	N/A			<0.01	<0.1	2	N/A		
8V3699RA/RJ	HL08-61	122400	Blank	N/A			<0.01	<0.1	2	N/A		
8V3633RA/RJ	HL08-62	122150	Blank	N/A			0.01	<0.1	1	N/A		
8V3671RA/RJ	HL08-62	122200	Blank	N/A			<0.01	<0.1	7	N/A		
8V3671RA/RJ	HL08-62	122250	Blank	N/A			<0.01	<0.1	2	N/A		
8V3671RA/RJ	HL08-62	122275	Blank	N/A			<0.01	<0.1	2	N/A		
8V3672RA/RJ	HL08-63	122425	Blank	N/A			<0.01	<0.1	7	N/A		
8V3672RA/RJ	HL08-63	122500	Blank	N/A			<0.01	<0.1	7	N/A		
8V3672RA/RJ	HL08-63	122525	Blank	N/A			<0.01	<0.1	13	N/A		
8V3699RA/RJ	HL08-63	122550	Blank	N/A			0.01	<0.1	6	N/A		

STANDARDS AND BLANKS

Certificate Number	Hole No.	Sample Number	Standard Number	WCM Values			Assayers Values			% Diff Assayers vs WCM		
				Au g/t	Ag g/t	Cu ppm	Au g/t	Ag g/t	Cu ppm	Au	Ag	Cu

PM197												
8V2297RA/RJ	HL08-03	48990	PM197	0.45	n/a	n/a	0.42	n/a	n/a	-6.67		
8V2690RA/RJ	HL08-16	84425	PM197	0.45	n/a	n/a	0.45	n/a	n/a	0.00		
8V2698RA/RJ	HL08-18	84700	PM197	0.45	n/a	n/a	0.48	n/a	n/a	6.67		
8V2768RA/RJ	HL08-23	85125	PM197	0.45	n/a	n/a	0.49	n/a	n/a	8.89		
8V2820RA/RJ	HL08-27	85375	PM197	0.45	n/a	n/a	0.46	n/a	n/a	2.22		
8V3081RA/RJ	HL08-34	120250	PM197	0.45	n/a	n/a	0.47	n/a	n/a	4.44		
8V3190RA/RJ	HL08-37	120525	PM197	0.45	n/a	n/a	0.44	n/a	n/a	-2.22		
8V3190RA/RJ	HL08-38	120675	PM197	0.45	n/a	n/a	0.47	n/a	n/a	4.44		
8V3283RA/RJ	HL08-41	125925	PM197	0.45	n/a	n/a	0.43	n/a	n/a	-4.44		
8V3298RA/RJ	HL08-45	120975	PM197	0.45	n/a	n/a	0.52	n/a	n/a	15.56		N/A
8V3497RA/RJ	HL08-47	130125	PM197	0.45	n/a	n/a	0.48	n/a	n/a	6.67		
8V3498RA/RJ	HL08-55	130275	PM197	0.45	n/a	n/a	0.50	n/a	n/a	11.11		
8V3551RA/RJ	HL08-55	130375	PM197	0.45	n/a	n/a	0.43	n/a	n/a	-4.44		
8V3613RA/RJ	HL08-55	130425	PM197	0.45	n/a	n/a	0.35	n/a	n/a	-22.22		
8V3551RA/RJ	HL08-56	121625	PM197	0.45	n/a	n/a	0.47	n/a	n/a	4.44		
8V3634RA/RJ	HL08-58	130550	PM197	0.45	n/a	n/a	0.46	n/a	n/a	2.22		
8V3633RA/RJ	HL08-59	121900	PM197	0.45	n/a	n/a	0.50	n/a	n/a	11.11		
8V3671RA/RJ	HL08-62	122225	PM197	0.45	n/a	n/a	0.46	n/a	n/a	2.22		
Avg Difference:										2.22		

PM922												
8V2349RA/RJ	HL08-04	83600	PM922	6.31	n/a	n/a	6.22	n/a	n/a	-1.43		
8V2690RA/RJ	HL08-16	84475	PM922	6.31	n/a	n/a	6.26	n/a	n/a	-0.79		
8V2768RA/RJ	HL08-23	85075	PM922	6.31	n/a	n/a	6.34	n/a	n/a	0.48		
8V2699RA/RJ	HL08-24	85175A	PM922	6.31	n/a	n/a	6.09	n/a	n/a	-3.49		
8V2936RA/RJ	HL08-32	120025	PM922	6.31	n/a	n/a	6.45	n/a	n/a	2.22		
8V3063RA/RJ	HL08-33	120175	PM922	6.31	n/a	n/a	6.25	n/a	n/a	-0.95		
8V3215RA/RJ	HL08-39	120775	PM922	6.31	n/a	n/a	5.99	n/a	n/a	-5.07		
8V3283RA/RJ	HL08-42	120800	PM922	6.31	n/a	n/a	6.38	n/a	n/a	1.11		
8V3298RA/RJ	HL08-44	120900	PM922	6.31	n/a	n/a	6.56	n/a	n/a	3.96		N/A
8V3298RA/RJ	HL08-45	120925	PM922	6.31	n/a	n/a	6.56	n/a	n/a	3.96		
8V3497RA/RJ	HL08-47	130175	PM922	6.31	n/a	n/a	6.38	n/a	n/a	1.11		
8V3374RA/RJ	HL08-48	121200	PM922	6.31	n/a	n/a	6.34	n/a	n/a	0.48		
8V3395RA/RJ	HL08-50	121275	PM922	6.31	n/a	n/a	6.23	n/a	n/a	-1.27		
8V3497RA/RJ	HL08-53	121500	PM922	6.31	n/a	n/a	5.81	n/a	n/a	-7.92		
8V3551RA/RJ	HL08-55	130325	PM922	6.31	n/a	n/a	6.86	n/a	n/a	8.72		
8V3613RA/RJ	HL08-56	121725	PM922	6.31	n/a	n/a	6.63	n/a	n/a	5.07		
Avg Difference:										0.39		

PM1110												
8V2229RA/RJ	HL08-01	48721	PM1110	1.79	166	3900	1.68	181.0	4196	-6.15	9.04	7.59
8V2278RA/RJ	HL08-01	48777	PM1110	1.79	166	3900	1.79	144.5	3420	0.00	-12.95	-12.31
8V2297RA/RJ	HL08-03	48936	PM1110	1.79	166	3900	1.75	165.0	4017	-2.23	-0.60	3.00
8V2376RA/RJ	HL08-06	83722	PM1110	1.79	166	3900	1.77	152.9	3607	-1.12	-7.89	-7.51
8V2472RA/RJ	HL08-11	84086	PM1110	1.79	166	3900	1.80	175.3	4169	0.56	5.60	6.90
8V2690RA/RJ	HL08-17	84600	PM1110	1.79	166	3900	1.42	155.0	3734	-20.67	-6.63	-4.26
8V2690RA/RJ	HL08-18	84650	PM1110	1.79	166	3900	1.68	174.0	3589	-6.15	4.82	-7.97
8V2768RA/RJ	HL08-20	84875	PM1110	1.79	166	3900	1.83	190.0	3787	2.23	14.46	-2.90
8V2768RA/RJ	HL08-22	84975	PM1110	1.79	166	3900	1.68	187.0	4169	-6.15	12.65	6.90
8V2821RA/RJ	HL08-25	85275	PM1110	1.79	166	3900	1.76	173.0	3519	-1.68	4.22	-9.77
8V3008RA/RJ	HL08-32	120075	PM1110	1.79	166	3900	1.82	193.0	3771	1.68	16.27	-3.31
8V3063RA/RJ	HL08-33	120125	PM1110	1.79	166	3900	1.76	160.0	3907	-1.68	-3.61	0.18
8V3081RA/RJ	HL08-35	120325	PM1110	1.79	166	3900	1.81	175.0	3674	1.12	5.42	-5.79
8V3100RA/RJ	HL08-36	120450	PM1110	1.79	166	3900	1.75	190.0	3904	-2.23	14.46	0.10
8V3190RA/RJ	HL08-37	120575	PM1110	1.79	166	3900	1.84	180.0	3705	2.79	8.43	-5.00
8V3283RA/RJ	HL08-41	125975	PM1110	1.79	166	3900	1.83	162.0	3534	2.23	-2.41	-9.38
8V3283RA/RD	HL08-43	120825	PM1110	1.79	166	3900	1.88	160.0	3739	5.03	-3.61	-4.13
8V3374RA/RJ	HL08-47	130025	PM1110	1.79	166	3900	1.85	159.0	3876	3.35	-4.22	-0.62
8V3498RA/RJ	HL08-54	121575	PM1110	1.79	166	3900	1.79	158.0	3661	0.00	-4.82	-6.13
8V3613RA/RJ	HL08-57	121775	PM1110	1.79	166	3900	1.84	186.0	3509	2.79	12.05	-10.03
Avg Difference:										-1.31	3.03	-3.22

PM1112												
8V2229RA/RJ	HL08-01	48747	PM1112	1.34	229	2300	1.26	232.0	2410	-5.97	1.31	4.78
8V2278RA/RJ	HL08-01	48812	PM1112	1.34	229	2300	1.24	234.3	2196	-7.46	2.31	-4.52

STANDARDS AND BLANKS

Certificate Number	Hole No.	Sample Number	Standard Number	WCM Values			Assayers Values			% Diff Assayers vs WCM		
				Au g/t	Ag g/t	Cu ppm	Au g/t	Ag g/t	Cu ppm	Au	Ag	Cu
8V2278RA/RJ	HL08-03	48861	PM1112	1.34	229	2300	1.43	237.0	2226	6.72	3.49	-3.22
8V2297RA/RJ	HL08-04	83528	PM1112	1.34	229	2300	1.33	227.0	2193	-0.75	-0.87	-4.65
8V2349RA/RJ	HL08-05	*83662	PM1112	1.34	229	2300	1.26	220.7	2227	-5.97	-3.62	-3.17
8V2415RA/RJ	HL08-08	83797	PM1112	1.34	229	2300	1.25	235.0	2097	-6.72	2.62	-8.83
8V2469RA/RJ	HL08-10	83927A	PM1112	1.34	229	2300	1.28	234.1	2311	-4.48	2.23	0.48
8V2472RA/RJ	HL08-10	84010A	PM1112	1.34	229	2300	1.33	231.9	2325	-0.75	1.27	1.09
8V2472RA/RJ	HL08-11	84027	PM1112	1.34	229	2300	1.36	226.9	2337	1.49	-0.92	1.61
8V2508RA/RJ	HL08-12	84155	PM1112	1.34	229	2300	1.31	232.5	2263	-2.24	1.53	-1.61
8V2508RA/RJ	HL08-12	84200	PM1112	1.34	229	2300	1.24	225.8	2297	-7.46	-1.40	-0.13
8V2558RA/RJ	HL08-13	84325	PM1112	1.34	229	2300	1.39	221.1	2275	3.73	-3.45	-1.09
8V2558RA/RJ	HL08-14	84277	PM1112	1.34	229	2300	1.39	218.1	2601	3.73	-4.76	13.09
8V2596RA/RJ	HL08-17	84525	PM1112	1.34	229	2300	1.32	230.3	2464	-1.49	0.57	7.13
8V2698RA/RJ	HL08-19	84800	PM1112	1.34	229	2300	1.02	220.3	2353	-23.88	-3.80	2.30
8V2768RA/RJ	HL08-22	85025	PM1112	1.34	229	2300	1.35	219.2	2420	0.75	-4.28	5.22
8V2768RA/RJ	HL08-24	85225	PM1112	1.34	229	2300	1.31	209.3	2007	-2.24	-8.60	-12.74
8V2819RA/RJ	HL08-29	85425	PM1112	1.34	229	2300	1.28	235.0	2247	-4.48	2.62	-2.30
8V3100RA/RJ	HL08-36	120400	PM1112	1.34	229	2300	1.40	223.7	2406	4.48	-2.31	4.61
8V3190RA/RJ	HL08-37	120625	PM1112	1.34	229	2300	1.50	213.7	2325	11.94	-6.68	1.09
Avg Difference:										-2.05	-1.14	-0.04

*83662 was rerun for Ag along with samples 83651-74 (original assay was 143 g/t Ag)

PM1116												
8V2596RA/RJ	HL08-15	84375	PM1116	n/a	722	n/a	n/a	744.1	n/a	N/A	3.06	N/A
8V2698RA/RP	HL08-18	84750	PM1116	n/a	722	n/a	n/a	790.0	n/a	N/A	9.42	N/A
8V2698RA/RJ	HL08-21	84925	PM1116	n/a	722	n/a	n/a	755.9	n/a	N/A	4.70	N/A
8V2821RA/RJ	HL08-25	85325	PM1116	n/a	722	n/a	n/a	792.5	n/a	N/A	9.76	N/A
8V3081RA/RJ	HL08-35	120275	PM1116	n/a	722	n/a	n/a	739.2	n/a	N/A	2.38	N/A
8V3215RA/RJ	HL08-38	120725	PM1116	n/a	722	n/a	n/a	803.7	n/a	N/A	11.32	N/A
8V3215RA/RJ	HL08-39	125825	PM1116	n/a	722	n/a	n/a	465.3	n/a	N/A	-35.55	N/A
8V3283RA/RJ	HL08-40	125875	PM1116	n/a	722	n/a	n/a	763.2	n/a	N/A	6.05	N/A
8V3298RA/RJ	HL08-46	121025	PM1116	n/a	722	n/a	n/a	765.7	n/a	N/A	6.50	N/A
8V3298RA/RJ	HL08-46	121075	PM1116	n/a	722	n/a	n/a	768.9	n/a	N/A	6.50	N/A
8V3395RA/RJ	HL08-47	130075	PM1116	n/a	722	n/a	n/a	797.4	n/a	N/A	10.44	N/A
8V3374RA/RJ	HL08-48	121150	PM1116	n/a	722	n/a	n/a	803.5	n/a	N/A	11.29	N/A
8V3395RA/RJ	HL08-52	121350	PM1116	n/a	722	n/a	n/a	774.6	n/a	N/A	7.29	N/A
8V3497RA/RJ	HL08-53	121400	PM1116	n/a	722	n/a	n/a	793.2	n/a	N/A	9.86	N/A
8V3497RA/RJ	HL08-53	121450	PM1116	n/a	722	n/a	n/a	785.5	n/a	N/A	8.80	N/A
8V3497RA/RJ	HL08-54	121525	PM1116	n/a	722	n/a	n/a	795.5	n/a	N/A	10.18	N/A
8V3497RA/RJ	HL08-55	130225	PM1116	n/a	722	n/a	n/a	791.8	n/a	N/A	9.67	N/A
8V3613RA/RJ	HL08-55	130475	PM1116	n/a	722	n/a	n/a	806.0	n/a	N/A	11.63	N/A
8V3551RA/RJ	HL08-56	121675	PM1116	n/a	722	n/a	n/a	287.7	n/a	N/A	-60.15	N/A
8V3613RA/RJ	HL08-57	121825	PM1116	n/a	722	n/a	n/a	793.0	n/a	N/A	9.83	N/A
8V3634RA/RJ	HL08-58	130600	PM1116	n/a	722	n/a	n/a	810.0	n/a	N/A	12.19	N/A
8V3634RA/RJ	HL08-58	130650	PM1116	n/a	722	n/a	n/a	806.5	n/a	N/A	11.70	N/A
8V3634RA/RJ	HL08-58	130700	PM1116	n/a	722	n/a	n/a	809.0	n/a	N/A	12.05	N/A
8V3633RA/RJ	HL08-59	121950	PM1116	n/a	722	n/a	n/a	801.0	n/a	N/A	10.94	N/A
8V3671RA/RJ	HL08-60	122025	PM1116	n/a	722	n/a	n/a	748.8	n/a	N/A	3.71	N/A
8V3671RA/RJ	HL08-60	122075	PM1116	n/a	722	n/a	n/a	792.1	n/a	N/A	9.71	N/A
8V3671RA/RJ	HL08-60	122125	PM1116	n/a	722	n/a	n/a	787.5	n/a	N/A	9.07	N/A
8V3633RA/RJ	HL08-62	122175	PM1116	n/a	722	n/a	n/a	800.0	n/a	N/A	10.80	N/A
Avg Difference:										4.76		

APPENDIX J

SAMPLE DESCRIPTIONS

Rock Sample Descriptions

Certificate Number	Sample Number	Zone	Easting NAD83	Northing NAD83	Sample Type	Width (m)	Sampler	Description	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V3081RA/RJ	Beach #1	Beach	435954	6223402	Grab		T. Kasum	black, fine grained, fine pyrite	0.01	<0.1	9	33	80
8V3081RA/RJ	Beach #2	Beach	435925	6223415	Grab		T. Kasum	black, fine grained, fine pyrite	0.03	0.1	2	23	49
8V2237RA	Bottom	Yellowstone	435010	6223620	Float		T. Kasum	rubblecrop, trench	3.57	1488.0	820	6300	14000
8V2615RA/RJ	PB08-01	49er	435215	6223432	Grab		P. Bilka	silicified, qtz veining, strong pyrite, trace gn	0.65	43.8	18	2630	899
8V2615RA/RJ	PB08-02	Oxidental	435268	6222739	Grab		P. Bilka	pale clay alt'd oc, ext. of (Paul's chips)	2.00	9.1	7	90	354
8V2615RA/RJ	PB08-03	Oxidental	435244	6222718	Grab		P. Bilka	pale clay alt'd oc, ext. of (Paul's chips)	0.57	6.7	15	141	88
8V2615RA/RJ	PB08-04	Below Summit	434724	6225134	Grab		P. Bilka	gossan, silicified andesite, qtz, pyrite, possible other sulfides	0.29	27.7	54	2097	3509
8V2615RA/RJ	PB08-05	Below Summit	434686	6225136	Grab		P. Bilka	gossan, silicified andesite, qtz, pyrite, possible other sulfides	0.10	13.3	28	132	223
8V2615RA/RJ	PB08-06	Below Summit	434676	6225117	Grab		P. Bilka	gossan, silicified andesite, qtz, pyrite, possible other sulfides	0.13	6.9	8	1443	4567
8V3063RA/RJ	PB0807	Beach	436211	6222848	Grab		P. Bilka	black, fine grained, fine pyrite	<0.01	0.3	6	21	233
8V3063RA/RJ	PB0808	Beach	436190	6222919	Grab		P. Bilka	black, fine grained, fine pyrite	<0.01	<0.1	7	16	74
8V3063RA/RJ	PB0809	Beach	436215	6222982	Grab		P. Bilka	black, fine grained, fine pyrite, some coarser limey bands	0.03	<0.1	13	39	167
8V3063RA/RJ	PB0810	Beach	436254	6223052	Grab		P. Bilka	black, fine grained, fine pyrite, some coarser limey bands	<0.01	<0.1	1	<2	25
8V3063RA/RJ	PB0811	Beach	436192	6223184	Grab		P. Bilka	black, fine grained, fine pyrite, some coarser limey bands	0.02	<0.1	4	16	53
8V3063RA/RJ	PB0812	Beach	436185	6223192	Grab		P. Bilka	black, fine grained, fine pyrite, some coarser limey bands	0.01	<0.1	<1	19	71
8V3063RA/RJ	PB0813	Beach	436108	6223315	Grab		P. Bilka	black, fine grained, fine pyrite	0.01	<0.1	7	13	118
8V3063RA/RJ	PB0814	Beach	436058	6223401	Grab		P. Bilka	black, fine grained, fine pyrite, some coarser limey bands	0.02	0.1	23	34	276
8V3063RA/RJ	PB0815	Beach	436021	6223504	Grab		P. Bilka	black, fine grained, fine pyrite, some coarser limey bands	0.04	0.2	3	17	39
8V3063RA/RJ	PB0816	Beach	435967	6223649	Grab		P. Bilka	black, fine grained, fine pyrite	0.01	<0.1	7	17	101
8V3063RA/RJ	PB0817	Beach	435986	6223785	Grab		P. Bilka	black, fine grained, fine pyrite, some coarser limey bands	<0.01	<0.1	<1	27	150
8V3063RA/RJ	PB0818	Troy	435196	6226307	Grab		P. Bilka	black, fine grained mst, fine qtz cb veinlets, 1-3% pyrite, pyrite clots	<0.01	<0.1	<1	46	111
8V3063RA/RJ	PB0819	Troy	435017	6226613	Grab		P. Bilka	black, fine grained mst, fine qtz cb veinlets, 1-3% pyrite, pyrite clots	<0.01	5.2	100	1203	791
8V3063RA/RJ	PB0820	Troy	435007	6226607	Grab		P. Bilka	black, fine grained mst, fine qtz cb veinlets, 1-3% pyrite, pyrite clots	0.02	<0.1	36	144	286
8V3063RA/RJ	PB0821	Troy	435007	6226607	Grab		P. Bilka	black, fine grained mst, 1-3% pyrite, pyrite clots	<0.01	<0.1	<1	30	99
8V3063RA/RJ	PB0822	Troy	435007	6226607	Grab		P. Bilka	black, fine grained mst, fine qtz cb veinlets, 1-3% pyrite, pyrite clots	<0.01	<0.1	<1	28	101
8V3063RA/RJ	PB0823	Troy	435007	6226607	Grab		P. Bilka	black, fine grained mst, fine qtz cb veinlets, 1-3% pyrite, pyrite clots	<0.01	<0.1	29	21	136
8V3063RA/RJ	PB0824	Troy	435291	6222515	Grab		P. Bilka	black, fine grained mst, 1-2% pyrite, pyrite clots	0.02	0.6	<1	49	158
8V3063RA/RJ	PB0825	Troy	435291	6222515	Grab		P. Bilka	black, fine grained mst, 1-3% pyrite, pyrite clots	<0.01	<0.1	<1	78	102
8V3374RA/RJ	PB0826	Sparky	434807	6224740	Grab		P. Bilka	andesite, silic, qtz stockwork, 1-3% pyrite, fine blue black seams	0.02	0.3	23	21	113
8V3374RA/RJ	PB0827	Sparky	435113	6222592	Grab		P. Bilka	qtz w/ fine blue black seams, pyrite	0.07	1.8	37	42	79
8V3374RA/RJ	PB0829	Sparky	434881	6222599	Grab		P. Bilka	qtz stckwk in andesite, pyrite, fine blue black seams	0.01	<0.1	42	19	143
8V3374RA/RJ	PB0830	Sparky	434882	6222613	Grab		P. Bilka	qtz w pyrite, fine blue black seams	0.02	<0.1	94	15	112
8V3374RA/RJ	PB0831	Sparky	434854	6224728	Grab		P. Bilka	silic andesite w qtz stockwork, pyrite	0.04	<0.1	13	12	87
8V3374RA/RJ	PB0832	Sparky	434867	6224642	Grab		P. Bilka	qtz w pyrite	0.01	<0.1	12	9	76
8V2892RA/RJ	PBSAM3	Sparky	435519	6222800	Grab		P. Bilka	qtz w pyrite, fine soft grey black mineral, sph, gn	8.10	4655.0	357	11600	12700
8V2892RA/RJ	PBSAM4	Sparky	435534	6222812	Grab		P. Bilka	silic andesite w pyrite	0.04	6.0	14	32	224
8V2892RA/RJ	PBSAM5	Sparky	435640	6222783	Grab		P. Bilka	silic andesite w pyrite	0.29	17.7	122	1991	1543
8V2892RA/RJ	PBSAM6	Sparky	435658	6222979	Grab		P. Bilka	silic andesite w pyrite	0.01	0.4	16	19	70
8V2892RA/RJ	PBSAM7	Sparky	435809	6222518	Grab		P. Bilka	silic andesite w pyrite	<0.01	1.6	19	45	110
8V3374RA/RJ	RS159	Road	434780	6224133	Grab		R. Shives	Dark green with abundant qtz carbonate veins, high K, low eTh.	0.01	<0.1	50	24	102
8V3374RA/RJ	RS108A	Sparky	435237	6222641	Grab		R. Shives	fine grained, bleached, light green, pyritic, volcanic	7.32	28.3	388	5400	14700
8V2820RA/RJ	Ruby	Sparky	435295	6222620	Grab		T. Kasum	white qtz w 2% pyrite, fine grey black min, sph, gn	5.31	3927.0	895	16300	43300
8V2297RA/RJ	SD0801	Yellowstone	435040	6223605	Grab		S. Deane	Trench Wall	1.58	464.9	82	3591	2780
8V2349RA/RJ	SD0802	49er	435261	6223369	Grab		S. Deane	Small Trench (800 series 2007)	0.98	13.3	15	50	5
8V2349RA/RJ	SD0803	Road	434712	6223317	Chip	0.70	S. Deane	70cm - fault zone, 118/20	0.31	12.8	552	390	1016
8V2508RA/RJ	SD0804	South Boundary	435090	6222247	Grab		S. Deane	5-10 cm soft FDM,py,gossan	0.01	3.3	23	44	116
8V2558RA/RJ	SD0805	Yellowstone	434821	6223605	Grab		S. Deane	7m qtz vn, py, gn, aspy?, soft FDM	0.09	21.4	256	7794	4640
8V2558RA/RJ	SD0806	Below Road	434649	6224102	Grab		S. Deane	5m wide oc, qtz vn stwk, py,gn,sph	0.20	11.6	84	7691	8842
8V2596RA/RJ	SD0807	Anaconda	435259	6222098	Grab		S. Deane	blast hole, qtz,ser,py gossan	0.69	35.2	28	247	1221
8V2596RA/RJ	SD0808	49er	435209	6223246	Grab		S. Deane	lg gossan, qtz,ser,py, malach, trend 085	6.17	103.0	420	11500	4681
8V2596RA/RJ	SD0809	Yellowstone	434795	6223356	Grab		S. Deane	qtz vn, 20-30cm, 045/30, py,sph,gn,cpy?	0.17	8.9	189	957	29900
8V2615RA/RJ	SD08-10	Below Summit	434710	6225154	Grab		S. Deane	blast bit, oc, str py ser qtz, gossan	0.90	67.4	27	4561	581
8V2892RA/RJ	SD08-11	Troy Gully	434955	6226600	Grab		S. Deane	Gossanous wall, fg sed w fg pyrite	0.01	<0.1	21	34	83
8V2892RA/RJ	SD08-12	Troy Gully	434958	6226606	Grab		S. Deane	1m wide fault, 220/80, mylonitic, gouge, rust	0.02	<0.1	7	18	127

Rock Sample Descriptions

Certificate Number	Sample Number	Zone	Easting NAD83	Northing NAD83	Sample Type	Width (m)	Sampler	Description	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V2892RA/RJ	SD08-13	Viper	434932	6223303	Grab		S. Deane	20-30cm qtz vn, flat lying, tr gn, tr mal, 250/10	0.05	8.8	655	238	17400
8V2892RA/RJ	SD08-14	Sparky	435084	6222253	Grab		S. Deane	qtz ser, jarosite yellow gossan, py, gn, euh py	0.07	4.0	35	54	188
8V3008RA/RJ	SD08-15	Dark Side	437858	6222920	Grab		S. Deane	qtz flt, rusty FeCb punk, several qtz peices	0.03	<0.1	20	4	34
8V3008RA/RJ	SD08-16	Dark Side	437902	6223642	Grab		S. Deane	qtz flt, several peices, vuggy, rusty FeCb	0.03	<0.1	5	14	23
8V3008RA/RJ	SD08-17	Dark Side	438261	6225396	Grab		S. Deane	qtz vn rubble near limey bed, runs~155,dips west, ~1m wide	0.02	<0.1	7	4	47
8V3008RA/RJ	SD08-18	Dark Side	438477	6225797	Grab		S. Deane	rusty mudstone, vfg py, grainy layers	0.03	<0.1	19	14	114
8V3100RA/RJ	SD08-19	Chicago	434837	6224001	Grab		S. Deane	qtz cc vn, ~090/-60, few cm's wide, 2% cpy, 1% gn, 2% py	0.27	33.0	3824	9001	13400
8V3215RA/RJ	SD08-20	Troy North	435629	6228237	Grab		S. Deane	fg slst, mst, mm-1cm clasts, rusty gossan, runs ~110, vf py, fine qtz/cb vnlt	0.01	<0.1	25	26	106
8V3283RA/RJ	SD08-21	Troy North	436095	6226932	Grab		S. Deane	qtz in black mst, no slfx, ribbon qtz w rusty rims, mm-30 qtz, ~130, dips west	0.01	<0.1	6	4	27
8V2615RA/RJ	Snow #1	Snow Show	435114	6223340	Grab		T. Kasum	qtz with fine grey black seams, pyrite, gn, sphalerite	1.68	2688.0	833	13200	14100
8V2615RA/RJ	Snow #2	Snow Show	435114	6223340	Grab		T. Kasum	qtz with fine grey black seams, pyrite, gn, sphalerite	0.30	96.8	666	10900	15900
8V2415RA/RJ	SP08-01	Silbak Premier	436894	6212286	Grab		R. Shives	Glory Hole grab for comparison with Gamma readings, silic, ser, py	87.40	4170.0	20	8558	21000
8V2237RA	Top	Yellowstone	435063	6223585	Float		T. Kasum	rubblecrop, trench	3.43	2073.0	300	11000	10500
8V2376RA/RJ	WDR08-01	Yellowstone	434901	6223632	Grab		W. Gruenwald	Open cut (4m @340°) of rusty siliceous volcanic with up to 10% py). Minor ga, sph	0.82	22.4	149	4448	1232
8V2415RA/RJ	WDR08-02	Beach	435921	6223904	Grab		W. Gruenwald	Grab, v. rusty pod in hetroolithic lapilli tuffs with 2-3% f.g. py	0.14	10.5	9	66	116
8V2415RA/RJ	WDR08-03	Big K	435485	6224288	Grab		W. Gruenwald	Grab from old "blast" pit exposing v. fractured, rusty, pyritic volcanic.	0.02	1.4	15	17	162
8V2698RA/RJ	WDR08-04	Chicago South	435227	6224053	Float		W. Gruenwald	Float (30cm) v. rusty pale grey f.g. clastic sediment with 4-5% vfg py	0.75	<0.1	39	15	107
8V2820RA/RJ	WDR08-04 EM	Em Anom North	436525	6228929	Grab		W. Gruenwald	Grab across 4 m of very fissile sediments at site of very strong EM anomaly.	0.09	4.7	246	3550	2723
8V2820RA/RJ	WDR08-05	Chicago	435314	6224125	Float		W. Gruenwald	Grab from float (to 30 cm) of pale green porphyry (intrusive?) 3-5% py.	0.01	<0.1	16	142	156
8V2820RA/RJ	WDR08-06	Chicago South	435387	6224108	Float		W. Gruenwald	Grab from float train of rusty pale grey, f. g. felsic volcanoclastic with 7-10 % vf py.	0.02	<0.1	14	171	184
8V2820RA/RJ	WDR08-07	Chicago	435450	6224338	Float		W. Gruenwald	Grab, float boulders in E-W moraine. Siliceous volc fragmental, 1st clasts, 5-10% py	0.02	<0.1	13	132	173
8V2820RA/RJ	WDR08-08	Chicago	435309	6224466	Grab		W. Gruenwald	Outcrop rusty f.g. felsic porphyritic intrusive (dike?) with 5-10 % dissem. py	0.04	1.2	109	1213	1434
8V2892RA/RJ	WDR08-09	Beach	436008	6223515	Grab		W. Gruenwald	Outcrop grab of v. rusty brecciated argillitewith fragments of v. f. g py	<0.01	<0.2	20	22	107
8V3395RA/RJ	WDR08-10	Viper	435222	6222630	Grab		W. Gruenwald	Grab of 20 cm angular float in area of Radiometric anomaly A34	1.23	127.0	255	5514	5406
8V3395RA/RJ	WDR08-11	Viper	435164	6222640	Grab		W. Gruenwald	Talus grab at L-1120; soil pit 2642. Very siliceous volcanic with py ,asp, ga,sph	146.00	2271.0	591	9498	4587
8V3374RA/RJ	WDR08-12	Viper	435193	6222710	Grab		W. Gruenwald	Grab from angular rusty green volcanic with 5-10% py, asp.	1.07	1.1	36	795	934
8V3374RA/RJ	WDR08-13	Viper	435215	6222735	Grab		W. Gruenwald	Grab from outcrop of pale green pyritic volcanic with 5% sulphides and suspect asp	0.80	0.8	14	50	37
8V3374RA/RJ	WDR08-14	49er	435180	6223065	Grab		W. Gruenwald	Chip sample from otc of very silicified pale green volcanic with dissem. py, ga, cpy.	4.88	4.9	311	3044	6028
8V3374RA/RJ	WDR08-15	Yellowstone	434855	6223630	Grab		W. Gruenwald	Grab from rusty qtz veined zone (1.5 metres wide, trend 134°) in andesite.	0.31	2.5	87	387	1073
8V3374RA/RJ	WDR08-16	Big K/ Road	434890	6224239	Grab		W. Gruenwald	Random grab along 10 m of Granduc road N of mineralized trenches.	0.34	7.8	92	2945	9871

Chip Sample Descriptions

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Sampler	Description	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
T08-01 (Yellowstone)												
8V2469RA/RJ	T08-01	139001	435069	6223585	1	R. Kennedy	rusty grey rock, quartz veining, pyrite	0.10	12.7	33	105	115
8V2469RA/RJ	T08-01	139002	Bearing: 190°		1	R. Kennedy	rusty grey rock, quartz veining, pyrite	0.51	624.0	72	3212	3463
8V2469RA/RJ	T08-01	139003			1	R. Kennedy	rusty grey rock, quartz veining, pyrite	0.45	14.8	56	3702	6710
8V2469RA/RJ	T08-01	139004			1	R. Kennedy	rusty grey rock, quartz veining, pyrite	0.20	8.6	8	241	308
8V2469RA/RJ	T08-01	139005			1	R. Kennedy	rusty grey rock, quartz veining, pyrite	0.11	3.5	<1	63	92
8V2469RA/RJ	T08-01	139006			1	R. Kennedy	rusty grey rock, quartz veining, pyrite	0.38	143.8	56	328	868
8V2469RA/RJ	T08-01	139007			1	R. Kennedy	rusty grey rock, quartz veining, pyrite	0.17	9.1	121	359	405
8V2469RA/RJ	T08-01	139008	435068	6223577	1	R. Kennedy	rusty grey rock, quartz veining, pyrite	0.39	26.9	132	2582	1701
8												
T08-02 (Yellowstone)												
8V2690RA/RJ	T08-02	139154	435018	6223616	1	R. Kennedy	gossan with strong quartz stockwork and >5% pyrite	1.03	240.4	32	1576	2672
8V2690RA/RJ	T08-02	139155	Bearing: 190°		1	R. Kennedy	gossan with strong quartz stockwork and >5% pyrite	0.74	42.4	81	2844	1423
8V2690RA/RJ	T08-02	139156	435017	6223613	1	R. Kennedy	gossan with strong quartz stockwork and >5% pyrite	0.58	42.0	35	2564	724
3												
T08-03 (Yellowstone)												
8V2690RA/RJ	T08-03	139157	435012	6223623	1	C. Burnett	grey white quartz-rich volcanic with pyrite	0.04	2.6	25	248	112
8V2690RA/RJ	T08-03	139158	Bearing: 170°		1	C. Burnett	grey white quartz-rich volcanic with pyrite	0.17	5.7	16	250	127
8V2690RA/RJ	T08-03	139159			1	C. Burnett	grey white quartz-rich volcanic with pyrite, strongest sulfides	1.17	128.0	80	3271	1744
8V2690RA/RJ	T08-03	139160			1	C. Burnett	grey white quartz-rich volcanic with pyrite, strongest sulfides	7.62	475.2	372	12400	12600
8V2690RA/RJ	T08-03	139161			1	C. Burnett	grey white quartz-rich volcanic with pyrite	0.95	269.5	90	4556	2692
8V2690RA/RJ	T08-03	139162			435013	6223617	1	C. Burnett	grey white quartz-rich volcanic with pyrite	0.74	206.7	67
6												
T08-04 (Yellowstone)												
8V2690RA/RJ	T08-04	139163	435040	6223604	1	C. Burnett	very rusty gossan with quartz and rich pyrite	0.21	6.9	13	112	61
8V2690RA/RJ	T08-04	139164	Bearing: 50°		1	C. Burnett	very rusty gossan with quartz and rich pyrite	0.35	5.3	8	128	107
8V2690RA/RJ	T08-04	139165			1	C. Burnett	very rusty gossan with quartz and rich pyrite	0.20	12.7	8	252	192
8V2690RA/RJ	T08-04	139166			1	C. Burnett	very rusty gossan with quartz and rich pyrite	0.34	6.4	<1	189	205
8V2690RA/RJ	T08-04	139167			1	C. Burnett	very rusty gossan with quartz and rich pyrite	0.24	4.3	8	109	134
8V2690RA/RJ	T08-04	139168			1	C. Burnett	very rusty gossan with quartz and rich pyrite	0.20	3.0	12	115	134
8V2690RA/RJ	T08-04	139169			1	C. Burnett	very rusty gossan with quartz and rich pyrite	0.59	132.0	8	55	77
8V2690RA/RJ	T08-04	139170			435046	6223609	1	C. Burnett	very rusty gossan with quartz and rich pyrite	0.10	34.1	22
8												
T08-05 (49er)												
8V2469RA/RJ	T08-05	139009	435090	6223471	1	R. Kennedy	rusty grey rock with quartz veinlets and strong pyrite, fine dark seams	8.82	12.1	149	616	568
8V2469RA/RJ	T08-05	139010	Bearing: 180°		1	R. Kennedy	rusty grey rock with quartz veinlets and strong pyrite, fine dark seams	10.31	10.0	192	357	221
8V2469RA/RJ	T08-05	139011			1	R. Kennedy	rusty grey rock with quartz veinlets and strong pyrite, fine dark seams	0.14	1.6	57	33	85
8V2469RA/RJ	T08-05	139012			1	R. Kennedy	rusty grey rock with quartz veinlets and strong pyrite, fine dark seams	0.14	2.1	81	41	108
8V2469RA/RJ	T08-05	139013			1	R. Kennedy	rusty grey rock with quartz veinlets and strong pyrite, fine dark seams	3.51	7.3	113	107	65
8V2469RA/RJ	T08-05	139014			1	R. Kennedy	rusty grey rock with quartz veinlets and strong pyrite, fine dark seams	0.10	3.6	125	17	75
8V2469RA/RJ	T08-05	139015			1	R. Kennedy	rusty grey rock with quartz veinlets and strong pyrite, fine dark seams	0.12	4.2	87	110	95
8V2469RA/RJ	T08-05	139016			1	R. Kennedy	rusty grey rock with quartz veinlets and strong pyrite, fine dark seams	0.12	3.9	86	37	98
8V2469RA/RJ	T08-05	139017			1	R. Kennedy	rusty grey rock with quartz veinlets and strong pyrite, fine dark seams	0.19	3.5	57	34	95
8V2469RA/RJ	T08-05	139018			1	R. Kennedy	rusty grey rock with quartz veinlets and strong pyrite, fine dark seams	0.79	834.0	71	1585	2699
8V2469RA/RJ	T08-05	139019			1	R. Kennedy	rusty grey rock with quartz veinlets and strong pyrite, fine dark seams	0.97	953.0	186	2274	4369

Chip Sample Descriptions

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Sampler	Description	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V2469RA/RJ	T08-05	139020			1	R. Kennedy	rusty grey rock with quartz veinlets and strong pyrite, fine dark seams	1.56	14.0	79	183	144
8V2469RA/RJ	T08-05	139021			1	R. Kennedy	rusty grey rock with quartz veinlets and strong pyrite, fine dark seams	0.60	17.9	171	72	114
8V2469RA/RJ	T08-05	139022			1	R. Kennedy	rusty grey rock with quartz veinlets and strong pyrite, fine dark seams	0.41	17.2	237	364	389
8V2469RA/RJ	T08-05	139023	435090	6223456	1	R. Kennedy	rusty grey rock with quartz veinlets and strong pyrite, fine dark seams	0.59	40.5	95	696	698
15												
T08-06 (Big K)												
8V2596RA/RJ	T08-06	139068	434660	6223929	1	C. Burnett	grey green rock with quartz veinlets, pyrite veinlets, galena.sphalerite vnlt	0.11	2.8	154	1077	1996
8V2596RA/RJ	T08-06	139069			1	C. Burnett	grey green rock with quartz veinlets, pyrite veinlets, galena.sphalerite vnlt	0.09	3.4	130	1312	934
8V2596RA/RJ	T08-06	139070			1	C. Burnett	grey green rock with quartz veinlets, pyrite veinlets, galena.sphalerite vnlt	0.20	16.5	997	5188	6437
8V2596RA/RJ	T08-06	139071			1	C. Burnett	grey green rock with quartz veinlets, pyrite veinlets, galena.sphalerite vnlt	0.15	16.5	352	7969	7763
8V2596RA/RJ	T08-06	139072			1	C. Burnett	grey green rock with quartz veinlets, pyrite veinlets, galena.sphalerite vnlt	0.67	36.5	2823	9900	12200
8V2596RA/RJ	T08-06	139073			1	C. Burnett	grey green rock with quartz veinlets, pyrite veinlets, galena.sphalerite vnlt	0.05	0.6	15	136	171
8V2596RA/RJ	T08-06	139074	434666	6223926	1	C. Burnett	grey green rock with quartz veinlets, pyrite veinlets, galena.sphalerite vnlt	0.05	0.6	15	164	127
7												
T08-07 (Big K)												
8V2596RA/RJ	T08-07	139075	434667	6223916	1	C. Burnett	grey green rock, quartz stockwork, pyrite, galena, sphalerite	0.03	0.5	14	67	471
8V2596RA/RJ	T08-07	139076			1	C. Burnett	grey green rock, quartz stockwork, pyrite, galena, sphalerite	0.08	2.3	77	1244	1838
8V2596RA/RJ	T08-07	139077			1	C. Burnett	grey green rock, quartz stockwork, pyrite, galena, sphalerite	0.20	5.2	230	2730	2636
8V2596RA/RJ	T08-07	139078			1	C. Burnett	grey green rock, quartz stockwork, pyrite, galena, sphalerite	0.04	1.5	41	287	517
8V2596RA/RJ	T08-07	139079			1	C. Burnett	grey green rock, quartz stockwork, pyrite, galena, sphalerite	0.05	0.6	39	151	401
8V2596RA/RJ	T08-07	139080			1	C. Burnett	grey green rock, quartz stockwork, pyrite, galena, sphalerite	0.06	0.6	32	102	352
8V2596RA/RJ	T08-07	139081			1	C. Burnett	grey green rock, quartz stockwork, pyrite, galena, sphalerite	0.06	0.7	23	137	265
8V2596RA/RJ	T08-07	139082	434661	6223911	1	C. Burnett	grey green rock, quartz stockwork, pyrite, galena, sphalerite	0.07	0.8	17	45	182
8												
T08-08 (Granduc Road)												
8V2596RA/RJ	T08-08	139083	434790	6222333	1	R. Kennedy	pale grey silicified rock with quartz veinlets, fine arsenopyrite	0.02	<0.1	9	74	237
8V2596RA/RJ	T08-08	139084			1	R. Kennedy	pale grey silicified rock with quartz veinlets, fine arsenopyrite	0.01	0.2	10	118	225
8V2596RA/RJ	T08-08	139085			1	R. Kennedy	pale grey silicified rock with quartz veinlets, fine arsenopyrite	<0.01	0.3	17	183	417
8V2596RA/RJ	T08-08	139086			1	R. Kennedy	pale grey silicified rock with quartz veinlets, fine arsenopyrite	0.02	0.7	46	755	759
8V2596RA/RJ	T08-08	139087			1	R. Kennedy	pale grey silicified rock with quartz veinlets, fine arsenopyrite	0.02	0.2	12	71	424
8V2596RA/RJ	T08-08	139088			1	R. Kennedy	pale grey silicified rock with quartz veinlets, fine arsenopyrite	0.03	0.5	18	195	921
8V2596RA/RJ	T08-08	139089			1	R. Kennedy	pale grey silicified rock with quartz veinlets, fine arsenopyrite	0.02	0.2	8	120	435
8V2596RA/RJ	T08-08	139090			1	R. Kennedy	pale grey silicified rock with quartz veinlets, fine arsenopyrite	0.03	0.5	32	319	1555
8V2596RA/RJ	T08-08	139091			1	R. Kennedy	pale grey silicified rock with quartz veinlets, fine arsenopyrite	0.03	1.5	103	1254	3856
8V2596RA/RJ	T08-08	139092			1	R. Kennedy	pale grey silicified rock with quartz veinlets, fine arsenopyrite	0.03	7.4	325	6264	8200
8V2596RA/RJ	T08-08	139093	434786	6222323	1	R. Kennedy	pale grey silicified rock with quartz veinlets, fine arsenopyrite	0.04	7.9	182	7520	8300
11												
T08-09 (Oxidantal)												
8V2596RA/RJ	T08-09	139094	435440	6222816	1	C. Burnett	grey silicified with strong pyrite, traces galena and sphalerite	0.08	9.6	15	87	117
8V2596RA/RJ	T08-09	139095			1	C. Burnett	grey silicified with strong pyrite, traces galena and sphalerite	1.36	1736.0	173	5314	10300
8V2596RA/RJ	T08-09	139096			1	C. Burnett	grey silicified with strong pyrite, traces galena and sphalerite	0.17	86.7	57	609	515
8V2596RA/RJ	T08-09	139097	435437	6222813	1	C. Burnett	grey silicified with strong pyrite, traces galena and sphalerite	0.06	5.8	21	51	112
4												
T08-10 (Granduc Road)												
8V2596RA/RJ	T08-10	139098	434656	6223478	1	P. Bilka	grey green volcanics, quartz veinlets, pyrite veinlets, trace galena/sphalerite	0.01	4.9	32	24	66

Chip Sample Descriptions

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Sampler	Description	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V2596RA/RJ	T08-10	139099	434670	6223469	1	P. Bilka	grey green volcanics, quartz veinlets, pyrite veinlets, trace galena/sphalerite	0.03	9.6	128	442	656
8V2596RA/RJ	T08-10	139100				P. Bilka	grey green volcanics, quartz veinlets, pyrite veinlets, trace galena/sphalerite	0.02	0.5	129	37	185
8V2596RA/RJ	T08-10	139101				P. Bilka	grey green volcanics, quartz veinlets, pyrite veinlets, trace galena/sphalerite	2.23	26.8	897	8186	101000
8V2596RA/RJ	T08-10	139102				P. Bilka	grey green volcanics, quartz veinlets, pyrite veinlets, trace galena/sphalerite	0.02	0.5	96	32	209
8V2596RA/RJ	T08-10	139103				P. Bilka	grey green volcanics, quartz veinlets, pyrite veinlets, trace galena/sphalerite	1.10	12.2	300	3235	81000
8V2596RA/RJ	T08-10	139104				P. Bilka	grey green volcanics, quartz veinlets, pyrite veinlets, trace galena/sphalerite	0.58	58.7	303	26400	4208
8V2596RA/RJ	T08-10	139105				P. Bilka	grey green volcanics, quartz veinlets, pyrite veinlets, trace galena/sphalerite	0.42	3.4	186	533	8758
8V2596RA/RJ	T08-10	139106				P. Bilka	grey green volcanics, quartz veinlets, pyrite veinlets, trace galena/sphalerite	0.03	0.8	66	187	891
8V2690RA/RJ	T08-10	139107				P. Bilka	grey green volcanics, quartz veinlets, pyrite veinlets, trace galena/sphalerite	0.21	2.9	84	455	1790
8V2690RA/RJ	T08-10	139108				P. Bilka	grey green volcanics, quartz veinlets, pyrite veinlets, trace galena/sphalerite	0.01	<0.1	99	47	112
8V2690RA/RJ	T08-10	139109				P. Bilka	grey green volcanics, quartz veinlets, pyrite veinlets, trace galena/sphalerite	0.01	<0.1	117	64	445
8V2690RA/RJ	T08-10	139110				P. Bilka	grey green volcanics, quartz veinlets, pyrite veinlets, trace galena/sphalerite	<0.01	<0.1	110	45	677
8V2690RA/RJ	T08-10	139111				P. Bilka	grey green volcanics, quartz veinlets, pyrite veinlets, trace galena/sphalerite	0.01	<0.1	117	35	367
8V2690RA/RJ	T08-10	139112				P. Bilka	grey green volcanics, quartz veinlets, pyrite veinlets, trace galena/sphalerite	0.03	0.2	90	160	333
8V2690RA/RJ	T08-10	139113				P. Bilka	grey green volcanics, quartz veinlets, pyrite veinlets, trace galena/sphalerite	0.01	<0.1	86	49	294
8V2690RA/RJ	T08-10	139114				P. Bilka	grey green volcanics, quartz veinlets, pyrite veinlets, trace galena/sphalerite	0.01	<0.1	86	56	319

17

T08-11 (Snow Show)												
8V2508RA/RJ	T08-11	139024	435116	6223348	1	C. Burnett	pale grey, strongly silicified, rusty, black seams, pyritic	0.15	14.0	219	1814	2194
8V2508RA/RJ	T08-11	139025	435114	6223342		C. Burnett	pale grey, strongly silicified, rusty, black seams, pyritic	0.25	27.6	239	3501	3302
8V2508RA/RJ	T08-11	139026				C. Burnett	pale grey, strongly silicified, rusty, black seams, pyritic	0.49	49.4	236	4865	4278
8V2508RA/RJ	T08-11	139027				C. Burnett	pale grey, strongly silicified, rusty, black seams, pyritic	0.18	17.6	312	3313	2734
8V2508RA/RJ	T08-11	139028				C. Burnett	pale grey, strongly silicified, rusty, black seams, pyritic	0.20	15.4	252	2680	2211
8V2508RA/RJ	T08-11	139029				C. Burnett	pale grey, strongly silicified, rusty, black seams, pyritic	0.27	17.2	331	2781	2028
6												
8V2508RA/RJ	T08-11	139030	435109	6223345	1	R. Kennedy	pale grey, strongly silicified, rusty, black seams, pyritic	0.23	10.8	129	485	287
8V2508RA/RJ	T08-11	139031	435114	6223348		R. Kennedy	pale grey, strongly silicified, rusty, black seams, pyritic	0.35	23.6	98	758	277
8V2508RA/RJ	T08-11	139032				R. Kennedy	pale grey, strongly silicified, rusty, black seams, pyritic	0.42	40.5	124	626	443
8V2508RA/RJ	T08-11	139033				R. Kennedy	pale grey, strongly silicified, rusty, black seams, pyritic	0.46	26.6	167	430	539
8V2508RA/RJ	T08-11	139034				R. Kennedy	pale grey, strongly silicified, rusty, black seams, pyritic	0.15	16.5	164	2080	2557
8V2508RA/RJ	T08-11	139035				R. Kennedy	pale grey, strongly silicified, rusty, black seams, pyritic	0.41	115.6	76	620	828

6

T08-12 (Paulet)												
8V2558RA/RJ	T08-12	139036	434939	6223661	1	C. Burnett	rusty gossan, grey silicified rock, quartz veinlets, strong pyrite stringers	1.69	10.3	81	1410	1219
8V2558RA/RJ	T08-12	139037	434939	6223661		C. Burnett	rusty gossan, grey silicified rock, quartz veinlets, strong pyrite stringers	1.93	12.3	86	1553	868
8V2558RA/RJ	T08-12	139038				C. Burnett	rusty gossan, grey silicified rock, quartz veinlets, strong pyrite stringers	1.13	5.2	116	601	2370
8V2558RA/RJ	T08-12	139039				C. Burnett	rusty gossan, grey silicified rock, quartz veinlets, strong pyrite stringers	0.90	6.5	85	312	516
8V2558RA/RJ	T08-12	139040				C. Burnett	rusty gossan, grey silicified rock, quartz veinlets, strong pyrite stringers	2.02	14.2	87	1737	1715
8V2558RA/RJ	T08-12	139041				C. Burnett	rusty gossan, grey silicified rock, quartz veinlets, strong pyrite stringers	2.13	14.6	33	506	232
8V2558RA/RJ	T08-12	139042				C. Burnett	rusty gossan, grey silicified rock, quartz veinlets, strong pyrite stringers	1.31	15.8	62	599	662
8V2558RA/RJ	T08-12	139043				C. Burnett	rusty gossan, grey silicified rock, quartz veinlets, strong pyrite stringers	0.71	6.4	92	1122	1308
8V2558RA/RJ	T08-12	139044				C. Burnett	rusty gossan, grey silicified rock, quartz veinlets, strong pyrite stringers	1.70	40.9	60	1789	522

Chip Sample Descriptions

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Sampler	Description	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V2558RA/RJ	T08-12	139045			1	C. Burnett	rusty gossan, grey silicified rock, quartz veinlets, strong pyrite stringers	0.74	5.5	62	454	414
8V2558RA/RJ	T08-12	139046	434931	6223654	1	C. Burnett	rusty gossan, grey silicified rock, quartz veinlets, strong pyrite stringers	1.62	3.1	23	196	177

11

T08-13 (Paulet)

8V2558RA/RJ	T08-13	139047	434862	6223715	1	C. Burnett	gossan with quartz veinlets, up to 10% pyrite veinlets	0.07	1.2	32	84	332
8V2558RA/RJ	T08-13	139048	Bearing: 130°		1	C. Burnett	gossan with quartz veinlets, up to 10% pyrite veinlets	0.28	22.8	651	2950	5530
8V2558RA/RJ	T08-13	139049			1	C. Burnett	gossan with quartz veinlets, up to 10% pyrite veinlets	0.73	12.9	94	2058	2538
8V2558RA/RJ	T08-13	139050	434865	6223712	1	C. Burnett	gossan with quartz veinlets, up to 10% pyrite veinlets	0.15	1.3	60	158	511

4

T08-14 (Yellowstone)

8V2558RA/RJ	T08-14	139051	434821	6223607	1	R. Kennedy	weakly rusty, silicified volcanics, quartz and 2-7% pyrite	0.09	12.7	237	1477	217
8V2558RA/RJ	T08-14	139052	Bearing: 230°		1	R. Kennedy	weakly rusty, silicified volcanics, quartz and 2-7% pyrite	0.32	60.6	791	9192	2600
8V2558RA/RJ	T08-14	139053			1	R. Kennedy	weakly rusty, silicified volcanics, quartz and 2-7% pyrite	0.28	20.3	319	3944	3163
8V2558RA/RJ	T08-14	139054			1	R. Kennedy	weakly rusty, silicified volcanics, quartz and 2-7% pyrite	0.14	11.1	49	1338	381
8V2558RA/RJ	T08-14	139055			1	R. Kennedy	weakly rusty, silicified volcanics, quartz and 2-7% pyrite	0.43	9.5	62	912	401
8V2558RA/RJ	T08-14	139056			1	R. Kennedy	weakly rusty, silicified volcanics, quartz and 2-7% pyrite	0.18	8.1	50	633	273
8V2558RA/RJ	T08-14	139057			1	R. Kennedy	weakly rusty, silicified volcanics, quartz and 2-7% pyrite	0.20	8.9	78	500	313
8V2558RA/RJ	T08-14	139058	434815	6223602	1	R. Kennedy	weakly rusty, silicified volcanics, quartz and 2-7% pyrite	0.23	6.4	67	247	164

8

T08-15 (Paulet)

8V2558RA/RJ	T08-15	139059	434749	6223724	1	P. Bilka	rusty gossan, strong silicification and pyrite throughout	0.10	1.5	86	103	375
8V2558RA/RJ	T08-15	139060	Bearing: 230°		1	P. Bilka	rusty gossan, strong silicification and pyrite throughout	1.33	56.5	929	27100	9500
8V2558RA/RJ	T08-15	139061			1	P. Bilka	rusty gossan, strong silicification and pyrite throughout	0.36	25.9	516	14200	15200
8V2558RA/RJ	T08-15	139062			1	P. Bilka	rusty gossan, strong silicification and pyrite throughout	0.24	18.7	360	10700	10000
8V2558RA/RJ	T08-15	139063	434745	6223721	1	P. Bilka	rusty gossan, strong silicification and pyrite throughout	0.20	9.2	169	3988	3917

5

T08-16 (Paulet)

8V2596RA/RJ	T08-16	139065	434766	6223709	1	C. Burnett	gossan, quartz veinlets, pyrite disseminated and as veinlets	0.41	23.7	784	9900	7169
8V2596RA/RJ	T08-16	139066	Bearing: 210°		1	C. Burnett	gossan, quartz veinlets, pyrite disseminated and as veinlets	0.36	12.8	263	6453	1708
8V2596RA/RJ	T08-16	139067	434765	6223706	1	C. Burnett	gossan, quartz veinlets, pyrite disseminated and as veinlets	0.28	5.8	95	2722	965

3

T08-17 (49er)

8V2690RA/RJ	T08-17	139115	435130	6223247	1	C. Burnett	rusty silicified rock, disseminated pyrite, dark seams (mineral?)	0.39	8.7	266	842	831
8V2690RA/RJ	T08-17	139116	Bearing: 123°		1	C. Burnett	rusty silicified rock, disseminated pyrite, dark seams (mineral?)	0.51	11.1	402	1265	1585
8V2690RA/RJ	T08-17	139117			1	C. Burnett	rusty silicified rock, disseminated pyrite, dark seams (mineral?)	0.41	13.4	295	2203	2447
8V2690RA/RJ	T08-17	139118			1	C. Burnett	rusty silicified rock, disseminated pyrite, dark seams (mineral?)	0.42	9.4	252	1102	728
8V2690RA/RJ	T08-17	139119			1	C. Burnett	rusty silicified rock, disseminated pyrite, dark seams (mineral?)	0.28	4.4	217	232	619
8V2690RA/RJ	T08-17	139120			435135	6223244	1	C. Burnett	rusty silicified rock, disseminated pyrite, dark seams (mineral?)	0.29	5.4	80

6

T08-18 (49er)

8V2690RA/RJ	T08-18	139121	435210	6223245	1	R. Kennedy	rusty oc, silicified andesitic volcanic, pyrite with occasional galena	0.66	16.5	284	1536	710
8V2690RA/RJ	T08-18	139122	Bearing: 220°		1	R. Kennedy	rusty oc, silicified andesitic volcanic, pyrite with occasional galena	2.15	40.2	247	2974	1177
8V2690RA/RJ	T08-18	139123			1	R. Kennedy	rusty oc, silicified andesitic volcanic, pyrite with occasional galena	0.74	51.0	511	9333	3099
8V2690RA/RJ	T08-18	139124			1	R. Kennedy	rusty oc, silicified andesitic volcanic, pyrite with occasional galena	3.09	96.9	838	13600	7016

Chip Sample Descriptions

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Sampler	Description	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V2690RA/RJ	T08-18	139125			1	R. Kennedy	rusty oc, silicified andesitic volcanic, pyrite with occasional galena	2.51	45.0	545	6946	6849
8V2690RA/RJ	T08-18	139126	435206	6223240	1	R. Kennedy	rusty oc, silicified andesitic volcanic, pyrite with occasional galena	5.99	115.0	404	10400	836

6

T08-19 (Below Helen)

8V2690RA/RJ	T08-19	139127	435320	6222816	1	R. Kennedy	moderately rusty oc on gully wall, quartz stockwork, moderate pyrite	0.18	2.6	18	144	119
8V2690RA/RJ	T08-19	139128			1	R. Kennedy	moderately rusty oc on gully wall, quartz stockwork, moderate pyrite	0.18	4.8	40	151	94
8V2690RA/RJ	T08-19	139129			1	R. Kennedy	moderately rusty oc on gully wall, quartz stockwork, moderate pyrite	0.29	5.5	57	150	143
8V2690RA/RJ	T08-19	139130			1	R. Kennedy	moderately rusty oc on gully wall, quartz stockwork, moderate pyrite	0.17	4.4	35	79	89
8V2690RA/RJ	T08-19	139131			1	R. Kennedy	moderately rusty oc on gully wall, quartz stockwork, moderate pyrite	0.13	4.2	37	67	75
8V2690RA/RJ	T08-19	139132			1	R. Kennedy	moderately rusty oc on gully wall, quartz stockwork, moderate pyrite	0.04	1.9	14	30	36
8V2690RA/RJ	T08-19	139133			1	R. Kennedy	moderately rusty oc on gully wall, quartz stockwork, moderate pyrite	0.13	7.1	30	33	34
8V2690RA/RJ	T08-19	139134			1	R. Kennedy	moderately rusty oc on gully wall, quartz stockwork, moderate pyrite	0.04	2.0	25	45	39
8V2690RA/RJ	T08-19	139135			1	R. Kennedy	moderately rusty oc on gully wall, quartz stockwork, moderate pyrite	0.08	3.0	22	29	21
8V2690RA/RJ	T08-19	139136			1	R. Kennedy	moderately rusty oc on gully wall, quartz stockwork, moderate pyrite	0.04	2.1	14	16	18
8V2690RA/RJ	T08-19	139137			1	R. Kennedy	moderately rusty oc on gully wall, quartz stockwork, moderate pyrite	0.24	2.9	12	14	11
8V2690RA/RJ	T08-19	139138			1	R. Kennedy	moderately rusty oc on gully wall, quartz stockwork, moderate pyrite	0.12	3.1	9	62	33
8V2690RA/RJ	T08-19	139139	435325	6222804	1	R. Kennedy	moderately rusty oc on gully wall, quartz stockwork, moderate pyrite	0.27	3.6	15	75	39

13

T08-20 (Granduc Road)

8V2690RA/RJ	T08-20	139140	434838	6222421	1	C. Burnett	grey green volcanic, moderately rusty, pyrite stringers, quartz stockwork	0.02	10.7	210	272	111
8V2690RA/RJ	T08-20	139141			1	C. Burnett	grey green volcanic, moderately rusty, pyrite stringers, quartz stockwork	0.01	0.5	99	19	97
8V2690RA/RJ	T08-20	139142			1	C. Burnett	grey green volcanic, moderately rusty, pyrite stringers, quartz stockwork	0.02	0.8	76	25	81
8V2690RA/RJ	T08-20	139143			1	C. Burnett	grey green volcanic, moderately rusty, pyrite stringers, quartz stockwork	<0.01	1.3	85	74	126
8V2690RA/RJ	T08-20	139144			1	C. Burnett	grey green volcanic, moderately rusty, pyrite stringers, quartz stockwork	0.02	0.7	82	30	104
8V2690RA/RJ	T08-20	139145			1	C. Burnett	grey green volcanic, moderately rusty, pyrite stringers, quartz stockwork	0.02	0.8	99	155	150
8V2690RA/RJ	T08-20	139146			1	C. Burnett	grey green volcanic, moderately rusty, pyrite stringers, quartz stockwork	0.02	0.2	96	27	92
8V2690RA/RJ	T08-20	139147	434835	6222413	1	C. Burnett	grey green volcanic, moderately rusty, pyrite stringers, quartz stockwork	<0.01	0.2	85	23	77

8

T08-21 (49er)

8V2690RA/RJ	T08-21	139148	435145	6223440	1	C. Burnett	rusty oc, silicified volcanic, stockwork, pyrite veinlets, dark seams	0.25	4.5	58	97	116
8V2690RA/RJ	T08-21	139149			1	C. Burnett	rusty oc, silicified volcanic, stockwork, pyrite veinlets, dark seams	0.38	4.0	30	307	452
8V2690RA/RJ	T08-21	139150			1	C. Burnett	rusty oc, silicified volcanic, stockwork, pyrite veinlets, dark seams	0.28	3.5	46	267	196
8V2690RA/RJ	T08-21	139151			1	C. Burnett	rusty oc, silicified volcanic, stockwork, pyrite veinlets, dark seams	0.56	9.2	46	891	754
8V2690RA/RJ	T08-21	139152			1	C. Burnett	rusty oc, silicified volcanic, stockwork, pyrite veinlets, dark seams	0.23	3.9	44	315	327
8V2690RA/RJ	T08-21	139153	435142	6223435	1	C. Burnett	rusty oc, silicified volcanic, stockwork, pyrite veinlets, dark seams	0.20	2.0	42	80	96

6

T08-22 (Oxidental)

8V2698RA/RJ	T08-22	139171	435263	6222737	1	C. Burnett	rusty zone, strong pyrite and silicification, grey andesite	0.06	3.8	19	79	72
8V2698RA/RJ	T08-22	139172			1	C. Burnett	rusty zone, strong pyrite and silicification, grey andesite	0.25	19.7	44	1680	2037
8V2698RA/RJ	T08-22	139173	435263	6222734	1	C. Burnett	rusty zone, strong pyrite and silicification, grey andesite	0.21	9.6	12	481	637

3

T08-23 (Granduc North)

8V2698RA/RJ	T08-23	139174	434706	6225150	1	P. Bilka	rusty road cut oc, dark grey black altered rick, jarositic, strong pyrite	1.29	36.1	11	919	309
8V2698RA/RJ	T08-23	139175			1	P. Bilka	rusty road cut oc, dark grey black altered rick, jarositic, strong pyrite	0.07	5.0	7	1026	586
8V2698RA/RJ	T08-23	139176			1	P. Bilka	rusty road cut oc, dark grey black altered rick, jarositic, strong pyrite	0.39	9.1	10	556	786

Chip Sample Descriptions

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Sampler	Description	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V2698RA/RJ	T08-23	139177	434704	6225147	1	P. Bilka	rusty road cut oc, dark grey black altered rick, jarositic, strong pyrite	2.81	127.0	12	1267	173
4												

T08-24 (Granduc North)

8V2698RA/RJ	T08-24	139178	434678	6225129	1	P. Bilka	rusty road cut oc, dark grey black altered rick, jarositic, strong pyrite	0.05	0.9	21	189	158
8V2698RA/RJ	T08-24	139179	Bearing: 210°		1	P. Bilka	rusty road cut oc, dark grey black altered rick, jarositic, strong pyrite	0.05	2.9	16	859	857
8V2698RA/RJ	T08-24	139180			1	P. Bilka	rusty road cut oc, dark grey black altered rick, jarositic, strong pyrite	0.07	1.5	18	206	320
8V2698RA/RJ	T08-24	139181			1	P. Bilka	rusty road cut oc, dark grey black altered rick, jarositic, strong pyrite	0.07	2.3	8	513	492
8V2698RA/RJ	T08-24	139182			1	P. Bilka	rusty road cut oc, dark grey black altered rick, jarositic, strong pyrite	0.04	1.7	24	533	505
8V2698RA/RJ	T08-24	139183			1	P. Bilka	rusty road cut oc, dark grey black altered rick, jarositic, strong pyrite	0.06	1.3	13	531	1036
8V2698RA/RJ	T08-24	139184			1	P. Bilka	rusty road cut oc, dark grey black altered rick, jarositic, strong pyrite	0.05	8.1	18	159	112
8V2698RA/RJ	T08-24	139185			434674	6225122	1	P. Bilka	rusty road cut oc, dark grey black altered rick, jarositic, strong pyrite	0.02	0.9	2
8												

T08-25 (Granduc North)

8V2698RA/RJ	T08-25	139186	434675	6225122	1	R. Kennedy	rusty road cut oc, grey silicified rock, strong pyrite	0.34	1.6	12	115	368
8V2698RA/RJ	T08-25	139187	Bearing: 210°		1	R. Kennedy	rusty road cut oc, grey silicified rock, strong pyrite	0.18	2.3	14	579	1131
8V2698RA/RJ	T08-25	139188			1	R. Kennedy	rusty road cut oc, grey silicified rock, strong pyrite	0.17	4.1	55	885	228
8V2698RA/RJ	T08-25	139189	434673	6225119	1	R. Kennedy	rusty road cut oc, grey silicified rock, strong pyrite	0.19	1.3	71	59	129
4												

T08-26 (Tangerine)

8V2698RA/RJ	T08-26	139190	434665	6224828	1	C. Burnett	bright orange rusty oc, strong disseminated pyrite, strong galena, fractured	0.31	1.3	59	22100	141		
8V2698RA/RJ	T08-26	139191	Bearing: 330°		1	C. Burnett	bright orange rusty oc, strong disseminated pyrite, strong galena, fractured	0.87	65.3	315	7666	436		
8V2698RA/RJ	T08-26	139192			1	C. Burnett	bright orange rusty oc, strong disseminated pyrite, strong galena, fractured	1.7	193.0	101	21400	1064		
8V2698RA/RJ	T08-26	139193			1	C. Burnett	bright orange rusty oc, strong disseminated pyrite, strong galena, fractured	1.82	141.0	120	30500	198		
8V2698RA/RJ	T08-26	139194			1	C. Burnett	bright orange rusty oc, strong disseminated pyrite, strong galena, fractured	0.57	175.0	176	94000	724		
8V2698RA/RJ	T08-26	139195			1	C. Burnett	bright orange rusty oc, strong disseminated pyrite, strong galena, fractured	0.64	232.7	118	114000	1794		
8V2698RA/RJ	T08-26	139196			1	C. Burnett	bright orange rusty oc, strong disseminated pyrite, strong galena, fractured	0.91	260.4	158	62000	1241		
8V2698RA/RJ	T08-26	139197			1	C. Burnett	bright orange rusty oc, strong disseminated pyrite, strong galena, fractured	1.29	207.7	646	39000	4280		
8V2698RA/RJ	T08-26	139198			1	C. Burnett	bright orange rusty oc, strong disseminated pyrite, strong galena, fractured	4.46	347.5	365	115000	5933		
8V2698RA/RJ	T08-26	139199			1	C. Burnett	bright orange rusty oc, strong disseminated pyrite, strong galena, fractured	1.17	319.6	143	26000	432		
8V2698RA/RJ	T08-26	139200			1	C. Burnett	bright orange rusty oc, strong disseminated pyrite, strong galena, fractured	0.28	237.3	105	3407	841		
8V2698RA/RJ	T08-26	139201			1	C. Burnett	bright orange rusty oc, strong disseminated pyrite, strong galena, fractured	0.16	53.2	55	1412	210		
8V2698RA/RJ	T08-26	139202			434659	6224839	1	C. Burnett	bright orange rusty oc, strong disseminated pyrite, strong galena, fractured	0.5	17.8	68	1412	228
13														

T08-27 (Tangerine)

8V2698RA/RJ	T08-27	139203	434673	6224784	1	C. Burnett	rusty fractured oc in pit (same as T08-26), disseminated pyrite	0.12	3.9	16	131	85
8V2698RA/RJ	T08-27	139204	Bearing: 260°		1	C. Burnett	rusty fractured oc in pit (same as T08-26), disseminated pyrite	0.06	3.4	14	75	111
8V2698RA/RJ	T08-27	139205			1	C. Burnett	rusty fractured oc in pit (same as T08-26), disseminated pyrite	0.32	5.3	10	81	69
8V2698RA/RJ	T08-27	139206			1	C. Burnett	rusty fractured oc in pit (same as T08-26), disseminated pyrite	0.10	1.9	8	93	163
8V2698RA/RJ	T08-27	139207			434668	6224783	1	C. Burnett	rusty fractured oc in pit (same as T08-26), disseminated pyrite	0.08	1.1	9
5												

T08-28 (Tangerine)

8V2698RA/RJ	T08-28	139208	434668	6224776	1	C. Burnett	rusty oc, disseminated pyrite, pale grey andesite	0.02	3.7	7	419	109
8V2698RA/RJ	T08-28	139209	Bearing: 260°		1	C. Burnett	rusty oc, disseminated pyrite, pale grey andesite	0.15	2.9	26	212	179
8V2698RA/RJ	T08-28	139210			434665	6224775	1	C. Burnett	rusty oc, disseminated pyrite, pale grey andesite	0.67	4.8	9
3												

Chip Sample Descriptions

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Sampler	Description	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm		
T08-29 (Tangerine)														
8V2698RA/RJ	T08-29	139211	434676	6224770	1	C. Burnett	rusty oc, pyrite stringers, silicified	0.18	1.9	3	133	15		
8V2698RA/RJ	T08-29	139212	Bearing: 260°		1	C. Burnett	rusty oc, pyrite stringers, silicified	0.29	19.7	15	1031	521		
8V2698RA/RJ	T08-29	139213	434673	6224769	1	C. Burnett	rusty oc, pyrite stringers, silicified	0.07	1.0	11	31	38		
3														
T08-30 (Tangerine)														
8V2698RA/RJ	T08-30	139214	434705	6224762	1	C. Burnett	rusty oc, disseminated pyrite, silicified	0.06	<0.1	28	24	89		
8V2698RA/RJ	T08-30	139215	Bearing: 190°		1	C. Burnett	rusty oc, disseminated pyrite, silicified	0.03	<0.1	25	17	94		
8V2698RA/RJ	T08-30	139216			1	C. Burnett	rusty oc, disseminated pyrite, silicified	0.09	<0.1	20	18	42		
8V2698RA/RJ	T08-30	139217	434704	6224758	1	C. Burnett	rusty oc, disseminated pyrite, silicified	<0.01	0.2	31	18	36		
4														
T08-31 (Granduc Road)														
8V2768RA/RJ	T08-31	139218	434637	6223543	1	R. Kennedy	grey green andesitic volcanic with 2-5% pyrite disseminated and as stringers	0.05	5.2	80	276	344		
8V2768RA/RJ	T08-31	139219	Bearing:190°		1	R. Kennedy	grey green andesitic volcanic with 2-5% pyrite disseminated and as stringers	0.02	1.8	159	56	366		
8V2768RA/RJ	T08-31	139220			1	R. Kennedy	grey green andesitic volcanic with 2-5% pyrite disseminated and as stringers	0.40	2.4	114	95	1021		
8V2768RA/RJ	T08-31	139221			1	R. Kennedy	grey green andesitic volcanic with 2-5% pyrite disseminated and as stringers	0.30	2.6	106	269	2292		
8V2768RA/RJ	T08-32	139222			1	R. Kennedy	grey green andesitic volcanic with 2-5% pyrite disseminated and as stringers	0.05	0.7	56	61	373		
8V2768RA/RJ	T08-31	139223			1	R. Kennedy	grey green andesitic volcanic with 2-5% pyrite disseminated and as stringers	1.51	3.4	165	274	2140		
8V2768RA/RJ	T08-31	139224			1	R. Kennedy	grey green andesitic volcanic with 2-5% pyrite disseminated and as stringers	0.23	2.1	56	199	1004		
8V2768RA/RJ	T08-31	139225			1	R. Kennedy	grey green andesitic volcanic with 2-5% pyrite disseminated and as stringers	0.14	2.0	52	215	2258		
8V2768RA/RJ	T08-31	139226			1	R. Kennedy	grey green andesitic volcanic with 2-5% pyrite disseminated and as stringers	0.16	1.4	93	103	353		
8V2768RA/RJ	T08-31	139227			1	R. Kennedy	grey green andesitic volcanic with 2-5% pyrite disseminated and as stringers	0.19	1.8	132	63	200		
8V2768RA/RJ	T08-31	139228			1	R. Kennedy	grey green andesitic volcanic with 2-5% pyrite disseminated and as stringers	0.16	1.8	138	105	423		
8V2768RA/RJ	T08-31	139229			1	R. Kennedy	grey green andesitic volcanic with 2-5% pyrite disseminated and as stringers	0.08	0.5	50	36	131		
8V2768RA/RJ	T08-31	139230			434635	6223530	1	R. Kennedy	grey green andesitic volcanic with 2-5% pyrite disseminated and as stringers	0.64	3.6	147	130	649
13														
T08-32 (Granduc Road)														
8V2768RA/RJ	T08-32	139231	434700	6223326	1	R. Kennedy	grey green volcanics, quartz stringers and pyrite throughout	0.16	2.4	138	263	234		
8V2768RA/RJ	T08-32	139232	Bearing: 129°		1	R. Kennedy	grey green volcanics, quartz stringers and pyrite throughout	0.06	<0.1	89	52	204		
8V2768RA/RJ	T08-32	139233			1	R. Kennedy	grey green volcanics, quartz stringers and pyrite throughout	0.04	<0.1	77	53	121		
8V2768RA/RJ	T08-32	139234			1	R. Kennedy	grey green volcanics, quartz stringers and pyrite throughout	0.03	<0.1	77	54	171		
8V2768RA/RJ	T08-32	139235			1	R. Kennedy	grey green volcanics, quartz stringers and pyrite throughout	0.02	<0.1	153	58	591		
8V2768RA/RJ	T08-32	139236			1	R. Kennedy	grey green volcanics, quartz stringers and pyrite throughout	0.04	<0.1	139	97	737		
8V2768RA/RJ	T08-32	139237			1	R. Kennedy	grey green volcanics, quartz stringers and pyrite throughout	0.07	<0.1	152	131	780		
8V2768RA/RJ	T08-32	139238			1	R. Kennedy	grey green volcanics, quartz stringers and pyrite throughout	0.04	<0.1	80	27	494		
8V2768RA/RJ	T08-32	139239			1	R. Kennedy	grey green volcanics, quartz stringers and pyrite throughout	0.04	<0.1	93	34	225		
8V2768RA/RJ	T08-32	139240			1	R. Kennedy	grey green volcanics, quartz stringers and pyrite throughout	0.02	0.2	56	266	286		
8V2768RA/RJ	T08-32	139241			1	R. Kennedy	grey green volcanics, quartz stringers and pyrite throughout	0.46	0.9	218	174	449		
8V2768RA/RJ	T08-32	139242			1	R. Kennedy	grey green volcanics, quartz stringers and pyrite throughout	0.12	4.9	367	3287	2036		
8V2768RA/RJ	T08-32	139243			1	R. Kennedy	grey green volcanics, quartz stringers and pyrite throughout	0.03	<0.1	96	372	748		
8V2768RA/RJ	T08-32	139244			1	R. Kennedy	grey green volcanics, quartz stringers and pyrite throughout	0.06	0.3	103	155	357		
8V2768RA/RJ	T08-32	139245			434712	6223317	1	R. Kennedy	grey green volcanics, quartz stringers and pyrite throughout	0.01	<0.1	124	45	292
15														
T08-33 (Granduc Road)														
8V2768RA/RJ	T08-33	139246	434830	6222994	1	R. Kennedy		<0.01	<0.1	72	19	145		

Chip Sample Descriptions

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Sampler	Description	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V2768RA/RJ	T08-33	139247	434833	6222984	1	R. Kennedy	grey green andesitic volcanics, pyritic, moderate quartz stockwork, some areas more silicified	<0.01	<0.1	100	12	106
8V2768RA/RJ	T08-33	139248			1	R. Kennedy		<0.01	<0.1	104	8	95
8V2768RA/RJ	T08-33	139249			1	R. Kennedy		0.01	<0.1	81	9	93
8V2768RA/RJ	T08-33	139250			1	R. Kennedy		<0.01	0.3	76	9	57
8V2768RA/RJ	T08-33	139251			1	R. Kennedy		0.02	0.5	81	18	86
8V2768RA/RJ	T08-33	139252			1	R. Kennedy		0.02	0.6	72	16	99
8V2768RA/RJ	T08-33	139253			1	R. Kennedy		0.01	1.7	95	82	72
8V2768RA/RJ	T08-33	139254			1	R. Kennedy		<0.01	1.6	66	19	81
8V2768RA/RJ	T08-33	139255	434833	6222984	1	R. Kennedy	<0.01	0.4	72	7	48	

10

T08-34 (Granduc Road)

8V3283RA/RJ	T08-34	139256	434826	6222405	1	P. Bilka	green andesite, silicified with 2-7% pyrite, tr gn, sph	0.01	0.5	34	10	81
8V3283RA/RJ	T08-34	139257	434826	6222405	1	P. Bilka	green andesite, silicified with 2-7% pyrite, tr gn, sph	<0.01	0.3	62	23	128
8V3283RA/RJ	T08-34	139258			1	P. Bilka	green andesite, silicified with 2-7% pyrite, tr gn, sph	<0.01	0.1	48	16	99
8V3283RA/RJ	T08-34	139259			1	P. Bilka	green andesite, silicified with 2-7% pyrite, tr gn, sph	0.02	0.5	85	24	115
8V3283RA/RJ	T08-34	139260			1	P. Bilka	green andesite, silicified with 2-7% pyrite, tr gn, sph	0.02	0.6	81	24	191
8V3283RA/RJ	T08-34	139261			1	P. Bilka	green andesite, silicified with 2-7% pyrite, tr gn, sph	0.05	2.1	128	900	731
8V3283RA/RJ	T08-34	139262			1	P. Bilka	green andesite, silicified with 2-7% pyrite, tr gn, sph	0.06	3.0	107	613	2965
8V3283RA/RJ	T08-34	139263			1	P. Bilka	green andesite, silicified with 2-7% pyrite, tr gn, sph	0.05	1.9	94	122	548
8V3283RA/RJ	T08-34	139264			1	P. Bilka	green andesite, silicified with 2-7% pyrite, tr gn, sph	0.02	2.4	79	1116	927
8V3283RA/RJ	T08-34	139265			1	P. Bilka	green andesite, silicified with 2-7% pyrite, tr gn, sph	0.02	1.3	106	136	447
8V3283RA/RJ	T08-34	139266			1	P. Bilka	green andesite, silicified with 2-7% pyrite, tr gn, sph	0.01	1.6	107	517	841
8V3283RA/RJ	T08-34	139267			1	P. Bilka	green andesite, silicified with 2-7% pyrite, tr gn, sph	0.02	2.5	96	302	448

12

T08-35 (Chicago South)

8V2768RA/RJ	T08-35	139268	435123	6224065	1	C. Burnett	rusty and pale grey silicified volcanics with strong pyrite, quartz stringers, sph, gn	0.71	35.9	40	356	670
8V2768RA/RJ	T08-35	139269	435119	6224064	1	C. Burnett		0.80	47.0	42	341	1034
8V2768RA/RJ	T08-35	139270			1	C. Burnett		0.88	57.2	47	311	641
8V2768RA/RJ	T08-35	139271	435119	6224064	1	C. Burnett		0.52	25.1	29	325	397

4

T08-36 (Chicago South)

8V2768RA/RJ	T08-36	139272	435067	6224046	1	C. Burnett	pale grey, rusty with strong pyrite disseminated and as stringers, silicified, quartz stockwork, tra sphalerite and galena	0.64	8.8	30	166	218
8V2768RA/RJ	T08-36	139273	435060	6224046	1	C. Burnett		5.27	712.5	141	4647	7557
8V2768RA/RJ	T08-36	139274			1	C. Burnett		0.97	49.7	104	555	2413
8V2768RA/RJ	T08-36	139275			1	C. Burnett		0.59	24.0	76	282	1173
8V2768RA/RJ	T08-36	139276			1	C. Burnett		0.76	11.5	69	244	736
8V2768RA/RJ	T08-36	139277			1	C. Burnett		0.77	40.0	49	242	267
8V2768RA/RJ	T08-36	139278	435060	6224046	1	C. Burnett		1.53	18.7	11	190	202

7

T08-37 (Chicago South)

8V2768RA/RJ	T08-37	139279	435076	6224052	1	R. Kennedy	grey silicified with moderate quartz stockwork, strong pyrite	0.12	7.0	52	111	420
8V2768RA/RJ	T08-37	139280	435074	6224052	1	R. Kennedy	grey silicified, quartz stockwork, pyrite, fine dark seams	0.38	37.8	45	99	244
							2					

T08-38 (Chicago South)

Chip Sample Descriptions

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Sampler	Description	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V2821RA/RJ	T08-38	139281	435177	6224064	1	R. Kennedy	pale grey green volcanics with strong pervasive quartz stockwork, strong pyrite disseminated, common dark seams, trace to few % galena and sphalerite, trace chalcopyrite	8.21	126.0	293	11600	11800
8V2821RA/RJ	T08-38	139282	Bearing 340	1	R. Kennedy	6.24		101.0	904	11500	23200	
8V2821RA/RJ	T08-38	139283		1	R. Kennedy	7.96		127.0	1250	9496	22900	
8V2821RA/RJ	T08-38	139284		1	R. Kennedy	11.30		126.0	1836	12500	36600	
8V2821RA/RJ	T08-38	139285		1	R. Kennedy	2.67		168.0	133	1541	2513	
8V2821RA/RJ	T08-38	139286	435175	6224070	1	R. Kennedy		4.34	176.0	64	1194	2747

6

T08-39 (Chicago South)

8V2821RA/RJ	T08-39	139287	435060	6224040	1	R. Kennedy	rusty oc, pale grey silicified, strong pyrite	0.56	47.9	12	189	157
8V2821RA/RJ	T08-39	139288	Bearing 270	1	R. Kennedy	rusty oc, pale grey silicified, strong pyrite	0.19	12.2	13	66	113	
8V2821RA/RJ	T08-39	139289		1	R. Kennedy	rusty oc, pale grey silicified, strong pyrite	1.73	271.9	42	1536	1670	
8V2821RA/RJ	T08-39	139290		1	R. Kennedy	rusty oc, pale grey silicified, strong pyrite	4.52	659.1	60	3495	3346	
8V2821RA/RJ	T08-39	139291		435055	6224040	1	R. Kennedy	rusty oc, pale grey silicified, strong pyrite	0.89	23.0	32	1085

5

T08-40 (Hammer)

8V2821RA/RJ	T08-40	139292	435099	6223778	1	T. Global	rusty oc, pale grey green andesite, strong stockwork, pyrite, sphalerite, trace galena	4.13	213.3	162	2025	5000
8V2821RA/RJ	T08-40	139293	Bearing 130	1	T. Global	4.26		243.7	87	2634	4010	
8V2821RA/RJ	T08-40	139294		1	T. Global	2.53		239.4	91	1693	2112	
8V2821RA/RJ	T08-40	139295	435102	6223775	1	T. Global		22.46	1281.0	476	3834	6338

4

T08-41 (Hammer)

8V2821RA/RJ	T08-41	139296	435098	6223769	1	T. Global	silicified, strong disseminated pyrite, fine sphalerite, galena, fine black seams, grey soft mineral common, strong quartz stockwork.	7.14	319.2	42	2747	649
8V2821RA/RJ	T08-41	139297	Bearing 134	1	T. Global	4.52		318.5	29	1725	291	
8V2821RA/RJ	T08-41	139298		1	T. Global	3.77		152.0	49	1020	882	
8V2821RA/RJ	T08-41	139299	435101	6223766	1	T. Global		3.20	158.0	19	1367	161

4

T08-42 (Paulet)

8V2821RA/RJ	T08-42	139300	434767	6223821	1	C. Burnett	rusty oc, grey green andesite, 5-15% pyrite as stringers and disseminated, trace galena, moderate silicification and stockwork.	0.52	9.6	200	2284	15400
8V2821RA/RJ	T08-42	139301	Bearing 139	1	C. Burnett	0.45		9.7	157	1349	3184	
8V2821RA/RJ	T08-42	139302		1	C. Burnett	0.74		9.4	175	2338	2057	
8V2821RA/RJ	T08-42	139303		1	C. Burnett	0.37		3.6	135	896	5242	
8V2821RA/RJ	T08-42	139304		1	C. Burnett	0.24		7.2	146	2896	5134	
8V2821RA/RJ	T08-42	139305	434771	6223816	1	C. Burnett		0.21	6.2	177	2843	3855

6

T08-43 (Paulet)

8V2821RA/RJ	T08-43	139306	434726	6223766	1	C. Burnett	pale grey volcanic, quartz stockwork, silicified, 2-5% pyrite	0.08	2.8	73	625	377
8V2821RA/RJ	T08-43	139307	Bearing 145	1	C. Burnett	pale grey volcanic, quartz stockwork, silicified, 2-5% pyrite	0.07	2.7	119	776	474	
8V2821RA/RJ	T08-43	139308		1	C. Burnett	pale grey volcanic, quartz stockwork, silicified, 2-5% pyrite	0.05	1.1	58	694	612	
8V2821RA/RJ	T08-43	139309		1	C. Burnett	pale grey volcanic, quartz stockwork, silicified, 2-5% pyrite	0.16	7.6	172	3561	711	
	T08-43	139310		434729	6223762	1	C. Burnett	pale grey volcanic, quartz stockwork, silicified, 2-5% pyrite	0.25	10.2	80	7682

Chip Sample Descriptions

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Sampler	Description	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
--------------------	---------------	---------------	---------------	----------------	-----------	---------	-------------	--------	--------	--------	--------	--------

5

T08-44 (Chicago South)

8V2821RA/RJ	T08-44	139311	435168	6224170	1	R. Kennedy	large rusty oc, pale grey green with moderate to strong silicification and quartz calcite stockwork, 2-10% pyrite, disseminated and as fine stringers, trace to few percent galena and sphalerite. Chip lines run roughly north south with richest looking rock in the middle.	0.22	16.0	19	942	1590
8V2821RA/RJ	T08-44	139312	Bearing 220		1	R. Kennedy		0.30	47.3	5	141	162
8V2821RA/RJ	T08-44	139313			1	R. Kennedy		0.31	15.9	8	90	82
8V2821RA/RJ	T08-44	139314			1	R. Kennedy		0.68	98.4	11	417	1865
8V2821RA/RJ	T08-44	139315			1	R. Kennedy		1.51	75.2	27	538	1396
8V2821RA/RJ	T08-44	139316			1	R. Kennedy		0.64	203.8	38	429	903
8V2821RA/RJ	T08-44	139317			1	R. Kennedy		20.73	198.0	27	805	2035
8V2821RA/RJ	T08-44	139318			1	R. Kennedy		0.39	25.1	15	105	180
8V2821RA/RJ	T08-44	139319			1	R. Kennedy		0.32	21.9	13	94	105
8V2821RA/RJ	T08-44	139320			1	R. Kennedy		0.44	38.6	19	173	239
8V2821RA/RJ	T08-44	139321			1	R. Kennedy		0.94	123.0	19	208	227
8V2821RA/RJ	T08-44	139322			1	R. Kennedy		1.04	49.8	20	125	118
8V2821RA/RJ	T08-44	139323	435160	6224160	1	R. Kennedy		0.70	29.7	27	125	366

13

T08-45 (Chicago South)

8V2820RA/RJ	T08-45	139324	435090	6224080	1	R. Kennedy	grey green andesite, silicified, pyritic, galena and sphalerite sporadic	0.10	10.2	10	126	156
8V2820RA/RJ	T08-45	139325	Bearing 220		1	R. Kennedy	grey green andesite, silicified, pyritic, galena and sphalerite sporadic	3.53	155.0	45	2169	1415
8V2820RA/RJ	T08-45	139326			1	R. Kennedy	grey green andesite, silicified, pyritic, galena and sphalerite sporadic	0.03	3.7	16	34	48
8V2820RA/RJ	T08-45	139327	435087	6224077	1	R. Kennedy	grey green andesite, silicified, pyritic, galena and sphalerite sporadic	0.40	6.1	24	85	127

4

T08-46 (Chicago South)

8V2820RA/RJ	T08-46	139328	435089	6224054	1	C. Burnett	rusty oc, grey green andesite, quartz stockwork, pyritic	0.37	12.7	20	95	217
8V2820RA/RJ	T08-46	139329	Bearing 220		1	C. Burnett	rusty oc, grey green andesite, quartz stockwork, pyritic	0.43	14.5	15	131	133
8V2820RA/RJ	T08-46	139330			1	C. Burnett	rusty oc, grey green andesite, quartz stockwork, pyritic	0.63	22.8	43	196	671
8V2820RA/RJ	T08-46	139331	435086	6224051	1	C. Burnett	rusty oc, grey green andesite, quartz stockwork, pyritic	0.58	27.5	32	152	324

4

T08-47 (Hammer)

8V2820RA/RJ	T08-47	139332	434888	6223870	1	C. Burnett	pale grey green andesite with pyrite and strong silicification	1.32	9.2	106	1854	2153
8V2820RA/RJ	T08-47	139333	Bearing 136		1	C. Burnett	pale grey green andesite with pyrite and strong silicification	11.82	42.4	45	2290	1271
8V2820RA/RJ	T08-47	139334	434890	6223868	1	C. Burnett	pale grey green andesite with pyrite and strong silicification	11.15	78.2	85	9961	1577

3

T08-48 (Hammer)

8V2820RA/RJ	T08-48	139335	434904	6223825	1	C. Burnett	quartz-rich, pyrite-rich, pale grey, traces sphalerite, galena	2.04	12.2	367	1699	9374
8V2820RA/RJ	T08-48	139336	Bearing 134		1	C. Burnett	quartz-rich, pyrite-rich, pale grey, traces sphalerite, galena	1.59	39.1	1487	5088	25500
8V2820RA/RJ	T08-48	139337	434906	6223823	1	C. Burnett	quartz-rich, pyrite-rich, pale grey, traces sphalerite, galena	1.56	55.5	853	4880	14700

3

Chip Sample Descriptions

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Sampler	Description	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
T08-49 (Paulet)												
8V2820RA/RJ	T08-49	139338	434825	6223705	1	P. Bilka	rusty oc, strong quartz stockwork and pyrite stringers, trace to few percent galena, sphalerite, and few clots of chalcopyrite with some malachite staining	0.58	28.8	395	18600	722
8V2820RA/RJ	T08-49	139339	Bearing 160		1	P. Bilka		0.99	17.7	143	7593	6145
8V2820RA/RJ	T08-49	139340			1	P. Bilka		0.78	13.9	165	2448	7140
8V2820RA/RJ	T08-49	139341	434826	6223701	1	P. Bilka		1.21	66.7	3643	49400	49800

4

T08-50 (Bee)												
8V2892RA/RJ	T08-50	139342	435318	6222553	1	R. Kennedy	rusty face, grey to dark green andesite with moderate quartz stockwork, 2-5% disseminated pyrite, bounded by dacitic and rhyolitic dikes.	0.19	1.7	6	24	63
8V2892RA/RJ	T08-50	139343	Bearing 118		1	R. Kennedy		0.04	2.0	4	42	48
8V2892RA/RJ	T08-50	139344			1	R. Kennedy		0.01	0.9	5	20	43
8V2892RA/RJ	T08-50	139345			1	R. Kennedy		0.06	1.8	4	24	27
8V2892RA/RJ	T08-50	139346			1	R. Kennedy		0.09	3.9	9	50	154
8V2892RA/RJ	T08-50	139347			1	R. Kennedy		0.28	6.0	6	34	20
8V2892RA/RJ	T08-50	139348			1	R. Kennedy		0.24	5.9	3	36	29
8V2892RA/RJ	T08-50	139349			1	R. Kennedy		0.06	1.5	7	17	41
8V2892RA/RJ	T08-50	139350			1	R. Kennedy		0.17	3.6	15	39	78
8V2892RA/RJ	T08-50	139351			435327	6222548		1	R. Kennedy	0.22	3.2	17

10

T08-51 (Bee)												
8V2892RA/RJ	T08-51	139352	435318	6222545	1	C. Burnett	rusty oc, green andesite with moderate quartz calcite stockwork, pyritic	0.15	3.5	7	42	39
8V2892RA/RJ	T08-51	139353	Bearing: 118°		1	C. Burnett	rusty oc, green andesite with moderate quartz calcite stockwork, pyritic	0.14	3.7	5	71	61
8V2892RA/RJ	T08-51	139354			1	C. Burnett	rusty oc, green andesite with moderate quartz calcite stockwork, pyritic	0.33	16.1	20	241	397
8V2892RA/RJ	T08-51	139355	435322	6222543	1	C. Burnett	rusty oc, green andesite with moderate quartz calcite stockwork, pyritic	1.37	348.8	39	1386	389

4

T08-52 (Sparky)												
8V2892RA/RJ	T08-52	139356	435283	6222509	1	C. Burnett	grey green blueish andesite, moderate quartz calcite sotckwork and sheeted veinlets, fine grey and blue black seams, 2-5% pyrite, tr-3% galena, tr-3% sphalerite	4.47	750.3	198	2069	2224
8V2892RA/RJ	T08-52	139357	Bearing: 180°		1	C. Burnett		1.91	1436.0	860	11800	23400
8V2892RA/RJ	T08-52	139358			1	C. Burnett		0.13	10.8	45	158	404
8V2892RA/RJ	T08-52	139359	435283	6222505	1	C. Burnett		1.18	554.2	272	3507	5839

4

T08-53 (Bee)												
8V2892RA/RJ	T08-53	139360	435294	6222554	1	R. Kennedy	grey green rusty, pyritic, siliceous and stockwork	1.91	105.0	129	1532	2881
8V2892RA/RJ	T08-53	139361	Bearing:165°		1	R. Kennedy	grey green rusty, pyritic, siliceous and stockwork	0.50	17.5	62	685	2184
8V2892RA/RJ	T08-53	139362			1	R. Kennedy	grey green rusty, pyritic, siliceous and stockwork	1.26	480.8	153	3003	4220
8V2892RA/RJ	T08-53	139363			1	R. Kennedy	grey green rusty, pyritic, siliceous and stockwork	1.43	144.0	72	3043	1557
8V2892RA/RJ	T08-53	139364			1	R. Kennedy	grey green rusty, pyritic, siliceous and stockwork	1.61	110.0	184	4757	3623
8V2892RA/RJ	T08-53	139365			1	R. Kennedy	grey green rusty, pyritic, siliceous and stockwork	0.81	319.0	72	555	719
8V2892RA/RJ	T08-53	139366			1	R. Kennedy	grey green rusty, pyritic, siliceous and stockwork	0.52	665.4	42	659	409
8V2892RA/RJ	T08-53	139367			1	R. Kennedy	grey green rusty, pyritic, siliceous and stockwork	1.23	397.2	59	689	1132
8V2892RA/RJ	T08-53	139368			1	R. Kennedy	grey green rusty, pyritic, siliceous and stockwork	0.30	7.1	17	52	64
8V2892RA/RJ	T08-53	139369			1	R. Kennedy	grey green rusty, pyritic, siliceous and stockwork	0.30	6.6	21	59	56

Chip Sample Descriptions

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Sampler	Description	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V2892RA/RJ	T08-53	139370			1	R. Kennedy	grey green rusty, pyritic, siliceous and stockwork	0.28	22.9	17	237	80
8V2892RA/RJ	T08-53	139371			1	R. Kennedy	grey green rusty, pyritic, siliceous and stockwork	0.22	6.8	17	60	35
8V2892RA/RJ	T08-53	139372	435297	6222541	1	R. Kennedy	grey green rusty, pyritic, siliceous and stockwork	0.66	9.4	30	120	307

13

T08-54 (Bee)												
8V2892RA/RJ	T08-54	139373	435283	6222556	1	R. Kennedy	andesite with pyrite disseminated and stringers, fine dark seams	0.91	499.7	41	1995	160
8V2892RA/RJ	T08-54	139374			1	R. Kennedy	andesite with pyrite disseminated and stringers, fine dark seams	0.97	145.0	81	798	855
8V2892RA/RJ	T08-54	139375			1	R. Kennedy	andesite with pyrite disseminated and stringers, fine dark seams	0.93	231.9	119	1068	565
8V2892RA/RJ	T08-54	139376			1	R. Kennedy	andesite with pyrite disseminated and stringers, fine dark seams	1.42	884.1	148	2333	2653
8V2892RA/RJ	T08-54	139377			1	R. Kennedy	andesite with pyrite disseminated and stringers, fine dark seams	0.75	97.2	45	935	218
8V2892RA/RJ	T08-54	139378			1	R. Kennedy	andesite with pyrite disseminated and stringers, fine dark seams	0.15	16.8	17	152	199
8V2892RA/RJ	T08-54	139379	435282	6222549	1	R. Kennedy	andesite with pyrite disseminated and stringers, fine dark seams	0.28	21.1	17	164	127

7

T08-55 (Sparky)												
8V2936RA/RJ	T08-55	139380	435299	6222496	1	C. Burnett	dark green rock, strong quartz flooding, up to 5% pyrite disseminated	0.38	6.6	26	79	68
8V2936RA/RJ	T08-55	139381			1	C. Burnett	dark green rock, strong quartz flooding, up to 5% pyrite disseminated	0.59	102.0	55	141	73
8V2936RA/RJ	T08-55	139382			1	C. Burnett	dark green rock, strong quartz flooding, up to 5% pyrite disseminated	0.32	2.8	39	28	74
8V2936RA/RJ	T08-55	139383			1	C. Burnett	dark green rock, strong quartz flooding, up to 5% pyrite disseminated	0.62	8.8	54	154	273
8V2936RA/RJ	T08-55	139384	435298	6222491	1	C. Burnett	dark green rock, strong quartz flooding, up to 5% pyrite disseminated	0.83	31.7	74	1157	1980

5

T08-56 (Sparky)												
8V2936RA/RJ	T08-56	139385	435333	6222455	1	C. Burnett	dark green grey andesite, quartz flooded, pyritic, trace galena and sphalerite	0.74	48.7	8	51	25
8V2936RA/RJ	T08-56	139386			1	C. Burnett	dark green grey andesite, quartz flooded, pyritic, trace galena and sphalerite	1.05	10.9	9	63	67
8V2936RA/RJ	T08-56	139387			1	C. Burnett	dark green grey andesite, quartz flooded, pyritic, trace galena and sphalerite	0.42	24.6	12	120	32
8V2936RA/RJ	T08-56	139388			1	C. Burnett	dark green grey andesite, quartz flooded, pyritic, trace galena and sphalerite	5.21	23.8	11	81	38
8V2936RA/RJ	T08-56	139389			1	C. Burnett	dark green grey andesite, quartz flooded, pyritic, trace galena and sphalerite	0.26	156.3	22	294	462
8V2936RA/RJ	T08-56	139390	435338	6222452	1	C. Burnett	dark green grey andesite, quartz flooded, pyritic, trace galena and sphalerite	0.31	45.4	25	67	35

6

T08-57 (Sparky)												
8V2936RA/RJ	T08-57	139391	435363	6222435	1	R. Kennedy	grey green andesite, moderate quartz stockwork, pyrite	0.11	2.7	22	61	151
8V2936RA/RJ	T08-57	139392			1	R. Kennedy	grey green andesite, moderate quartz stockwork, pyrite	0.21	3.3	13	63	82
8V2936RA/RJ	T08-57	139393			1	R. Kennedy	grey green andesite, moderate quartz stockwork, pyrite	0.19	9.3	12	108	105
8V2936RA/RJ	T08-57	139394			1	R. Kennedy	grey green andesite, moderate quartz stockwork, pyrite	0.12	8.0	17	79	144
8V2936RA/RJ	T08-57	139395	435363	6222440	1	R. Kennedy	grey green andesite, moderate quartz stockwork, pyrite	0.22	2.8	6	31	35

5

T08-58 (Sparky)												
8V2936RA/RJ	T08-58	139396	435285	6222505	1	R. Kennedy	rusty oc, grey green andesite, quartz stockwork, 2-4% fine disseminated py	0.56	36.8	61	963	477
8V2936RA/RJ	T08-58	139397			1	R. Kennedy	rusty oc, grey green andesite, quartz stockwork, 2-4% fine disseminated py	0.26	8.7	41	162	209
			435285	6222503		R. Kennedy						

2

T08-59 (Sparky)												
8V3008RA/RJ	T08-59	139398	435299	6222524	1	P. Bilka		0.41	4.6	2	64	24
8V3008RA/RJ	T08-59	139399			1	P. Bilka		0.54	284.7	3	918	87

Chip Sample Descriptions

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Sampler	Description	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V3008RA/RJ	T08-59	139400	435309	6222509	1	P. Bilka	long chip line of grey green andesite with moderate silicification and quartz calcite stockwork, 2-7% pyrite disseminated and as veinlets, sporadic sphalerite and galena up to 3%, chip line is bounded by a quartz eye rhyolite dike to the north	0.62	193.0	36	1173	1213
8V3008RA/RJ	T08-59	139401				P. Bilka		0.25	10.6	2	60	39
8V3008RA/RJ	T08-59	139402				P. Bilka		0.30	5.7	6	41	38
8V3008RA/RJ	T08-59	139403				P. Bilka		0.29	8.6	12	32	21
8V3008RA/RJ	T08-59	139404				P. Bilka		0.50	6.7	2	37	18
8V3008RA/RJ	T08-59	139405				P. Bilka		0.33	9.1	5	61	51
8V3008RA/RJ	T08-59	139406				P. Bilka		0.32	21.2	9	279	83
8V3008RA/RJ	T08-59	139407				P. Bilka		1.46	24.0	19	418	131
8V3008RA/RJ	T08-59	139408				P. Bilka		0.25	4.3	1	107	14
8V3008RA/RJ	T08-59	139409				P. Bilka		0.15	8.2	<1	356	22
8V3008RA/RJ	T08-59	139410				P. Bilka		0.27	12.3	<1	887	11
8V3008RA/RJ	T08-59	139411				P. Bilka		0.23	23.8	9	469	102
8V3008RA/RJ	T08-59	139412				P. Bilka		0.20	7.5	12	259	142
8V3008RA/RJ	T08-59	139413				P. Bilka		0.25	7.7	24	274	276
8V3008RA/RJ	T08-59	139414				P. Bilka		0.21	5.3	17	279	120
8V3008RA/RJ	T08-59	139415				435309		6222509	1	P. Bilka	0.34	5.6

18

T08-60 (Big K)

8V3008RA/RJ	T08-60	139416	434650	6224110	1	R. Kennedy	grey green andesite, moderate quartz pyrite stockwork, trace-4% sphalerite and galena as disseminated clots	0.12	8.2	147	4781	6252
8V3008RA/RJ	T08-60	139417	434642	6224106	1	R. Kennedy		0.12	6.9	54	4208	4666
8V3008RA/RJ	T08-60	139418			1	R. Kennedy		0.13	16.2	121	10600	15100
8V3008RA/RJ	T08-60	139419			1	R. Kennedy		0.12	8.5	82	5320	4943
8V3008RA/RJ	T08-60	139420			1	R. Kennedy		0.11	8.7	77	4953	4225
8V3008RA/RJ	T08-60	139421			1	R. Kennedy		0.11	12.0	236	6327	7980
8V3008RA/RJ	T08-60	139422			1	R. Kennedy		0.17	10.0	63	5954	7259
8V3008RA/RJ	T08-60	139423			1	R. Kennedy		0.21	17.6	220	6901	6737
8V3008RA/RJ	T08-60	139424	434642	6224106	1	R. Kennedy		0.05	6.5	80	3182	4423

9

T08-61 (Big K)

8V3008RA/RJ	T08-61	139425	434603	6223946	1	C. Burnett	grey, hard, quartz veinlets, pyrite stringer, trace galena and sphalerite	0.13	18.3	317	6325	4172
8V3008RA/RJ	T08-61	139426	434606	6223943	1	C. Burnett	grey, hard, quartz veinlets, pyrite stringer, trace galena and sphalerite	0.33	36.1	1081	15400	9135
8V3008RA/RJ	T08-61	139427			1	C. Burnett	grey, hard, quartz veinlets, pyrite stringer, trace galena and sphalerite	0.47	25.6	884	8355	9600
8V3008RA/RJ	T08-61	139428	434606	6223943	1	C. Burnett	grey, hard, quartz veinlets, pyrite stringer, trace galena and sphalerite	0.08	4.2	102	991	1136

4

T08-62 (Big K)

8V3008RA/RJ	T08-62	139429	434645	6223965	1	C. Burnett	grey, hard, quartz veinlets, pyrite stringer, trace galena and sphalerite	0.06	2.9	68	696	401
8V3008RA/RJ	T08-62	139430	434647	6223959	1	C. Burnett	grey, hard, quartz veinlets, pyrite stringer, trace galena and sphalerite	0.11	21.4	283	10100	3505
8V3008RA/RJ	T08-62	139431			1	C. Burnett	grey, hard, quartz veinlets, pyrite stringer, trace galena and sphalerite	0.24	2.9	61	1341	895
8V3008RA/RJ	T08-62	139432			1	C. Burnett	grey, hard, quartz veinlets, pyrite stringer, trace galena and sphalerite	0.17	10.9	172	4720	4073
8V3008RA/RJ	T08-62	139433			1	C. Burnett	grey, hard, quartz veinlets, pyrite stringer, trace galena and sphalerite	0.33	38.0	196	13800	758
8V3008RA/RJ	T08-62	139434	434647	6223959	1	C. Burnett	grey, hard, quartz veinlets, pyrite stringer, trace galena and sphalerite	0.13	7.9	59	2714	1637

6

T08-63 (Anaconda)

Chip Sample Descriptions

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Sampler	Description	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V3008RA/RJ	T08-63	139451	435090	6222252	1	R. Kennedy	rusty oc / pit in scree slope, grey green volcanic, some jarosite staining, seams of blue black soft mineral, disseminated pyrite and medium grained pyrite stringers	0.04	1.9	58	109	166
8V3008RA/RJ	T08-63	139452	Bearing: 240°		1	R. Kennedy		0.02	1.5	23	78	71
8V3008RA/RJ	T08-63	139453			1	R. Kennedy		0.04	2.0	43	43	101
8V3008RA/RJ	T08-63	139454			1	R. Kennedy		0.03	1.9	78	47	173
8V3008RA/RJ	T08-63	139455			1	R. Kennedy		0.03	1.9	36	68	144
8V3008RA/RJ	T08-63	139456			1	R. Kennedy		0.04	2.1	42	71	221
8V3008RA/RJ	T08-63	139457			1	R. Kennedy		0.04	1.8	15	55	160
8V3008RA/RJ	T08-63	139458	435083	6222248	1	R. Kennedy		0.03	1.3	11	24	87
					8							

T08-64 (Anaconda)												
8V3008RA/RJ	T08-64	139459	435091	6222267	1	C. Burnett	rusty oc on scree slope, silicified grey andesite, disseminated pyrite	0.02	1.3	59	18	114
8V3008RA/RJ	T08-64	139460	Bearing: 200°		1	C. Burnett	rusty oc on scree slope, silicified grey andesite, disseminated pyrite	0.01	1.6	36	20	64
8V3008RA/RJ	T08-64	139461			1	C. Burnett	rusty oc on scree slope, silicified grey andesite, disseminated pyrite	0.01	2.1	42	25	95
8V3008RA/RJ	T08-64	139462			1	C. Burnett	rusty oc on scree slope, silicified grey andesite, disseminated pyrite	0.04	2.5	71	31	108
8V3008RA/RJ	T08-64	139463			1	C. Burnett	rusty oc on scree slope, silicified grey andesite, disseminated pyrite	0.02	3.1	57	33	77
8V3008RA/RJ	T08-64	139464			1	C. Burnett	rusty oc on scree slope, silicified grey andesite, disseminated pyrite	0.01	2.1	36	22	65
8V3008RA/RJ	T08-64	139465	435089	6222260	1	C. Burnett	rusty oc on scree slope, silicified grey andesite, disseminated pyrite	0.03	2.3	48	23	99
					7							

T08-65 (Anaconda)												
8V3008RA/RJ	T08-65	139466	435091	6222279	1	C. Burnett	brown rusty volcanic, grey siliceous, pyritic	0.04	2.7	46	67	121
8V3008RA/RJ	T08-65	139467	Bearing: 195°		1	C. Burnett	brown rusty volcanic, grey siliceous, pyritic	0.03	1.1	68	47	73
8V3008RA/RJ	T08-65	139468			1	C. Burnett	brown rusty volcanic, grey siliceous, pyritic	0.02	1.4	7	36	23
8V3008RA/RJ	T08-65	139469			435090	6222275	1	C. Burnett	brown rusty volcanic, grey siliceous, pyritic	0.01	0.6	19
					4							

T08-66 (Gerry's)												
8V3063RA/RJ	T08-66	139435	435012	6223474	1	R. Kennedy	NS trenched rock face just north of Swiss Chalet Fault, grey strongly silicified volcanic, moderate quartz stockwork throughout, 2-7% pyrite disseminated and as stringers, 1-3% disseminated brown black sphalerite, trace-2% galena disseminated, dark black seams.	1.99	7.2	<1	924	3260
8V3063RA/RJ	T08-66	139436	Bearing: 160°		1	R. Kennedy		1.47	15.9	<1	1672	3109
8V3063RA/RJ	T08-66	139437			1	R. Kennedy		0.41	9.2	113	1008	12200
8V3063RA/RJ	T08-66	139438			1	R. Kennedy		0.39	2.3	80	1399	8359
8V3063RA/RJ	T08-66	139439			1	R. Kennedy		0.08	0.8	<1	266	860
8V3063RA/RJ	T08-66	139440			1	R. Kennedy		0.49	19.7	152	12300	1949
8V3063RA/RJ	T08-66	139441			1	R. Kennedy		1.67	136.0	723	33800	9751
8V3063RA/RJ	T08-66	139442			1	R. Kennedy		1.42	34.0	1268	2219	20900
8V3063RA/RJ	T08-66	139443			1	R. Kennedy		1.06	69.3	4287	13500	24400
8V3063RA/RJ	T08-66	139444	435015	6223465	1	R. Kennedy		2.31	39.4	759	3569	11700
					10							

T08-67 (Sparky)												
8V3063RA/RJ	T08-67	139445	435301	6222535	1	T. Global	Grey green volcanic, moderate quartz calcite stockwork, 2-4% diss. Pyrite	0.12	6.1	67	548	664
8V3063RA/RJ	T08-67	139446	Bearing: 148°		1	T. Global	Grey green volcanic, moderate quartz calcite stockwork, 2-4% diss. Pyrite	0.11	3.1	16	89	42
8V3063RA/RJ	T08-67	139447			1	T. Global	Grey green volcanic, moderate quartz calcite stockwork, 2-4% diss. Pyrite	0.23	4.2	20	269	127
8V3063RA/RJ	T08-67	139448			1	T. Global	Grey green volcanic, moderate quartz calcite stockwork, 2-4% diss. Pyrite	0.21	5.0	7	46	35
8V3063RA/RJ	T08-67	139449			435304	6222531	1	T. Global	Grey green volcanic, moderate quartz calcite stockwork, 2-4% diss. Pyrite	0.23	4.9	7
					5							

T08-68 (Sparky)												
8V3063RA/RJ	T08-68	139450	435395	6222477	1	T. Global	Grey-dark green rock, silicified with moderate quartz stockwork, 2-5% diss py	0.01	0.3	10	5	122

Chip Sample Descriptions

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Sampler	Description	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V3063RA/RJ	T08-68	139470			1	T. Global	Grey-dark green rock, silicified with moderate quartz stockwork, 2-5% diss py	0.03	0.7	14	18	68
8V3063RA/RJ	T08-68	139471			1	T. Global	Grey-dark green rock, silicified with moderate quartz stockwork, 2-5% diss py	0.04	0.5	12	6	62
8V3063RA/RJ	T08-68	139472			1	T. Global	Grey-dark green rock, silicified with moderate quartz stockwork, 2-5% diss py	0.07	0.7	8	19	33
8V3063RA/RJ	T08-68	139473			1	T. Global	Grey-dark green rock, silicified with moderate quartz stockwork, 2-5% diss py	0.03	0.6	14	13	101
8V3063RA/RJ	T08-68	139474			1	T. Global	Grey-dark green rock, silicified with moderate quartz stockwork, 2-5% diss py	<0.01	0.5	13	14	131
8V3063RA/RJ	T08-68	139475			1	T. Global	Grey-dark green rock, silicified with moderate quartz stockwork, 2-5% diss py	<0.01	0.3	12	6	86
8V3063RA/RJ	T08-68	139476			1	T. Global	Grey-dark green rock, silicified with moderate quartz stockwork, 2-5% diss py	0.01	0.5	11	7	59

8

T08-69 (Annalise)

8V3100RA/RJ	T08-69	139501	434938	6224007	1	C. Burnett		11.90	454.8	131	9806	8317
8V3100RA/RJ	T08-69	139502			1	C. Burnett		1.28	93.2	88	1231	2459
8V3100RA/RJ	T08-69	139503			1	C. Burnett		0.17	23.2	46	260	431
8V3100RA/RJ	T08-69	139504			1	C. Burnett	rusty oc, strongly silicified, strong stockwork, 1-3% diss pyrite, tr-2% phalerite and galena disseminated, fine grey seams	0.62	29.3	62	563	1653
8V3100RA/RJ	T08-69	139505			1	C. Burnett		6.67	412.0	86	4930	5180
8V3100RA/RJ	T08-69	139506			1	C. Burnett		0.19	11.7	21	193	282
8V3100RA/RJ	T08-69	139507			1	C. Burnett		1.75	105.0	44	1603	1518
8V3100RA/RJ	T08-69	139508			1	C. Burnett		0.06	1.6	40	28	113
8V3100RA/RJ	T08-69	139509			1	C. Burnett		0.08	2.7	69	39	81
8V3100RA/RJ	T08-69	139510			1	C. Burnett		0.02	0.7	70	11	131
8V3100RA/RJ	T08-69	139511			1	C. Burnett		0.04	0.6	61	6	194
8V3100RA/RJ	T08-69	139512			1	C. Burnett		0.35	2.5	28	48	33
8V3100RA/RJ	T08-69	139513			1	C. Burnett	rusty and grey green volcanic, moderate stockwork, not as juicy looking as above, 2-5% disseminated pyrite, possible traces sphalerite and galena	0.04	1.6	48	60	71
8V3100RA/RJ	T08-69	139514			1	C. Burnett		0.26	2.6	19	41	49
8V3100RA/RJ	T08-69	139515			1	C. Burnett		0.11	1.9	25	38	38
8V3100RA/RJ	T08-69	139516			1	C. Burnett		0.03	0.8	26	30	45
8V3100RA/RJ	T08-69	139517			1	C. Burnett		0.05	0.7	54	29	186
8V3100RA/RJ	T08-69	139518			1	C. Burnett		0.03	0.8	30	27	86
8V3100RA/RJ	T08-69	139519	434920	6224013	1	C. Burnett		0.14	1.7	33	133	138

19

T08-70 (Big K)

8V3215RA/RJ	T08-70	139520	434841	6224003	1	C. Burnett	Grey - dark green volcanic, moderate quartz stockwork, diss pyrite	0.21	3.0	224	343	1279
8V3215RA/RJ	T08-70	139521			1	C. Burnett	Grey - dark green volcanic, moderate quartz stockwork, diss pyrite	0.70	4.2	226	728	1255
8V3215RA/RJ	T08-70	139522	434838	6224003	1	C. Burnett	Grey - dark green volcanic, moderate quartz stockwork, diss pyrite	0.26	7.0	322	2255	7424

3

T08-71 (Big K)

8V3215RA/RJ	T08-71	139523	434787	6224011	1	C. Burnett	grey green rock, 2-5% pyrite disseminated, silicified	0.42	4.6	205	1282	314
8V3215RA/RJ	T08-71	139524			1	C. Burnett	grey green rock, 2-5% pyrite disseminated, silicified	0.50	5.0	179	801	252
8V3215RA/RJ	T08-71	139525			1	C. Burnett	grey green rock, 2-5% pyrite disseminated, silicified	0.33	4.5	159	1283	473
8V3215RA/RJ	T08-71	139526			1	C. Burnett	grey green rock, 2-5% pyrite disseminated, silicified	0.45	3.8	193	587	837
8V3215RA/RJ	T08-71	139527			1	C. Burnett	grey green rock, 2-5% pyrite disseminated, silicified	0.37	2.6	110	547	299
8V3215RA/RJ	T08-71	139528			1	C. Burnett	grey green rock, 2-5% pyrite disseminated, silicified	0.30	1.9	126	70	255
8V3215RA/RJ	T08-71	139529	434787	6224004	1	C. Burnett	grey green rock, 2-5% pyrite disseminated, silicified	0.16	2.4	239	67	480

7

T08-72 (Granduc Road North)

8V3215RA/RJ	T08-72	139478	434620	6226338	1	R. Kennedy		0.06	1.0	37	45	92
-------------	--------	--------	--------	---------	---	------------	--	------	-----	----	----	----

Chip Sample Descriptions

Certificate Number	Trench Number	Sample Number	Easting NAD83	Northing NAD83	Width (m)	Sampler	Description	Au g/t	Ag g/t	Cu ppm	Pb ppm	Zn ppm
8V3215RA/RJ	T08-72	139479			1	R. Kennedy		0.02	0.6	19	16	52
8V3215RA/RJ	T08-72	139480			1	R. Kennedy		0.04	0.6	20	22	68
8V3215RA/RJ	T08-72	139481			1	R. Kennedy		0.12	0.3	7	79	78
8V3215RA/RJ	T08-72	139482			1	R. Kennedy		0.13	0.5	16	72	137
8V3215RA/RJ	T08-72	139483			1	R. Kennedy		0.04	0.6	7	120	247
8V3215RA/RJ	T08-72	139484			1	R. Kennedy		0.03	0.6	15	10	49
8V3215RA/RJ	T08-72	139485			1	R. Kennedy		0.02	0.8	11	11	43
8V3215RA/RJ	T08-72	139486			1	R. Kennedy		0.05	0.8	54	11	55
8V3215RA/RJ	T08-72	139487			1	R. Kennedy		0.10	0.9	36	41	380
8V3215RA/RJ	T08-72	139488			1	R. Kennedy		0.02	1.2	16	15	27
8V3215RA/RJ	T08-72	139489			1	R. Kennedy		0.01	0.7	13	9	53
8V3283RA/RJ	T08-72	139490			1	R. Kennedy		0.05	1.0	25	82	177
8V3283RA/RJ	T08-72	139491			1	R. Kennedy		0.02	0.6	25	12	89
8V3283RA/RJ	T08-72	139492			1	R. Kennedy		0.08	0.5	27	13	69
8V3283RA/RJ	T08-72	139493			1	R. Kennedy	long rusty jarositic oc, grey andisitic rock, intermittently silicified, intermittent	0.07	0.3	35	7	102
8V3283RA/RJ	T08-72	139494			1	R. Kennedy	quartz calcite stockwork, common larger white and black calcite veins, very fine	0.03	0.5	31	12	87
8V3283RA/RJ	T08-72	139495		Bearing 180	1	R. Kennedy	grained grey seams and pods likely mudstone in volcanic, rich stringers and massive	0.05	0.6	19	18	61
8V3283RA/RJ	T08-72	139496			1	R. Kennedy	pods of fine to coarse grained pyrite, fine soft black seams possibly argillite.	0.09	0.8	36	65	69
8V3283RA/RJ	T08-72	139497			1	R. Kennedy		0.05	0.9	35	300	170
8V3283RA/RJ	T08-72	139498			1	R. Kennedy		0.02	0.5	21	14	76
8V3283RA/RJ	T08-72	139499			1	R. Kennedy		0.02	0.4	30	10	107
8V3283RA/RJ	T08-72	139500			1	R. Kennedy		0.02	0.4	52	27	128
8V3283RA/RJ	T08-72	139530			1	R. Kennedy		0.07	0.5	26	34	56
8V3283RA/RJ	T08-72	139531			1	R. Kennedy		0.03	0.5	24	29	59
8V3283RA/RJ	T08-72	139532			1	R. Kennedy		0.02	0.5	34	20	55
8V3283RA/RJ	T08-72	139533			1	R. Kennedy		0.02	0.3	31	9	104
8V3283RA/RJ	T08-72	139534			1	R. Kennedy		0.01	0.4	32	9	89
8V3283RA/RJ	T08-72	139535			1	R. Kennedy		<0.01	0.2	36	7	82
8V3283RA/RJ	T08-72	139536			1	R. Kennedy		0.01	0.3	23	50	79
8V3283RA/RJ	T08-72	139537			1	R. Kennedy		0.01	1.1	32	27	87
8V3283RA/RJ	T08-72	139538			1	R. Kennedy		0.01	<0.1	25	9	83
8V3283RA/RJ	T08-72	139539			1	R. Kennedy		0.02	0.3	34	7	79
8V3283RA/RJ	T08-72	139540	434620	6226304	1	R. Kennedy		0.02	1.1	11	26	23

APPENDIX K

ANALYTICAL CERTIFICATES AND PROCEDURES

LIST OF ANALYTICAL CERTIFICATES FOR THE 2008 DILWORTH EXPLORATION PROGRAM

LAB	CERTIFICATE NUMBER	DATE
Assayers Canada	8V2229RA	23-Jun-08
Assayers Canada	8V2229RJ	23-Jun-08
Assayers Canada	8V2237RA	17-Jun-08
Assayers Canada	8V2278RA	04-Jul-08
Assayers Canada	8V2278RJ	04-Jul-08
Assayers Canada	8V2297RA	09-Jul-08
Assayers Canada	8V2297RJ	09-Jul-08
Assayers Canada	8V2297RM	09-Jul-08
Assayers Canada	8V2349RA	12-Jul-08
Assayers Canada	8V2349RJ	12-Jul-08
Assayers Canada	8V2376RA	16-Jul-08
Assayers Canada	8V2376RJ	16-Jul-08
Assayers Canada	8V2415RA	18-Jul-08
Assayers Canada	8V2415RJ	18-Jul-08
Assayers Canada	8V2469RA	21-Jul-08
Assayers Canada	8V2469RJ	21-Jul-08
Assayers Canada	8V2472RA	22-Jul-08
Assayers Canada	8V2472RJ	22-Jul-08
Assayers Canada	8V2508RA	30-Jul-08
Assayers Canada	8V2508RJ	30-Jul-08
Assayers Canada	8V2558RA	01-Aug-08
Assayers Canada	8V2558RJ	01-Aug-08
Assayers Canada	8V2596RA	06-Aug-08
Assayers Canada	8V2596RJ	06-Aug-08
Assayers Canada	8V2615RA	24-Jul-08
Assayers Canada	8V2615RJ	24-Jul-08
Assayers Canada	8V2631RA	19-Aug-08
Assayers Canada	8V2631RJ	19-Aug-08
Assayers Canada	8V2690RA	13-Aug-08
Assayers Canada	8V2690RJ	13-Aug-08
Assayers Canada	8V2698RA	15-Aug-08
Assayers Canada	8V2698RJ	15-Aug-08
Assayers Canada	8V2698RP	15-Aug-08
Assayers Canada	8V2699RA	08-Aug-08
Assayers Canada	8V2699RJ	08-Aug-08
Assayers Canada	8V2768RA	27-Aug-08
Assayers Canada	8V2768RJ	27-Aug-08
Assayers Canada	8V2768RP	27-Aug-08
Assayers Canada	8V2819RA	12-Aug-08
Assayers Canada	8V2819RJ	12-Aug-08
Assayers Canada	8V2820RA	22-Aug-08
Assayers Canada	8V2820RJ	22-Aug-08
Assayers Canada	8V2821RA	20-Aug-08
Assayers Canada	8V2821RJ	20-Aug-08
Assayers Canada	8V2892RA	04-Sep-08
Assayers Canada	8V2892RJ	04-Sep-08
Assayers Canada	8V2892SG	04-Sep-08
Assayers Canada	8V2892SJ	04-Sep-08
Assayers Canada	8V2936RA	04-Sep-08
Assayers Canada	8V2936RJ	04-Sep-08
Assayers Canada	8V3008RA	04-Sep-08
Assayers Canada	8V3008RJ	04-Sep-08
Assayers Canada	8V3008SG	04-Sep-08
Assayers Canada	8V3008SJ	04-Sep-08

LIST OF ANALYTICAL CERTIFICATES FOR THE 2008 DILWORTH EXPLORATION PROGRAM

LAB	CERTIFICATE NUMBER	DATE
Assayers Canada	8V3063RA	19-Sep-08
Assayers Canada	8V3063RJ	19-Sep-08
Assayers Canada	8V3081RA	16-Sep-08
Assayers Canada	8V3081RJ	16-Sep-08
Assayers Canada	8V3081SG	16-Sep-08
Assayers Canada	8V3081SJ	16-Sep-08
Assayers Canada	8V3100RA	17-Sep-08
Assayers Canada	8V3100RJ	17-Sep-08
Assayers Canada	8V3100SG	17-Sep-08
Assayers Canada	8V3100SJ	17-Sep-08
Assayers Canada	8V3190RA	15-Sep-08
Assayers Canada	8V3190RJ	15-Sep-08
Assayers Canada	8V3190SG	15-Sep-08
Assayers Canada	8V3190SJ	15-Sep-08
Assayers Canada	8V3215RA	25-Sep-08
Assayers Canada	8V3215RJ	25-Sep-08
Assayers Canada	8V3283RA	30-Sep-08
Assayers Canada	8V3283RJ	30-Sep-08
Assayers Canada	8V3283RD	30-Sep-08
Assayers Canada	8V3298RA	26-Sep-08
Assayers Canada	8V3298RJ	26-Sep-08
Assayers Canada	8V3374RA	03-Oct-08
Assayers Canada	8V3374RJ	03-Oct-08
Assayers Canada	8V3395RA	09-Oct-08
Assayers Canada	8V3395RJ	09-Oct-08
Assayers Canada	8V3497RA	09-Oct-08
Assayers Canada	8V3497RJ	09-Oct-08
Assayers Canada	8V3498RA	10-Oct-08
Assayers Canada	8V3498RJ	10-Oct-08
Assayers Canada	8V3551RA	16-Oct-08
Assayers Canada	8V3551RJ	16-Oct-08
Assayers Canada	8V3613RA	21-Oct-08
Assayers Canada	8V3613RJ	21-Oct-08
Assayers Canada	8V3613SG	21-Oct-08
Assayers Canada	8V3613SJ	21-Oct-08
Assayers Canada	8V3633RA	23-Oct-08
Assayers Canada	8V3633RJ	23-Oct-08
Assayers Canada	8V3634RA	24-Oct-08
Assayers Canada	8V3634RJ	24-Oct-08
Assayers Canada	8V3671RA	28-Oct-08
Assayers Canada	8V3671RJ	28-Oct-08
Assayers Canada	8V3672RA	04-Nov-08
Assayers Canada	8V3672RJ	04-Nov-08
Assayers Canada	8V3699RA	05-Nov-08
Assayers Canada	8V3699RJ	05-Nov-08

Procedure Summary:

Gold (Au) Fire Assay

Elements Analyzed:

Gold (Au) – g/tonne

Procedure:

Lead flux and a silver inquart are added to the sample and mixed. Samples are fused in batches of 22 assays along with a natural standard and a reagent blank. This batch of 24 assays is carried through the whole procedure as a set.

After cupellation (which removes lead), the precious metal bead is parted in nitric acid to remove the silver. The remaining gold bead is either weighed (gravimetric finish) or dissolved in aqua regia and analyzed on an atomic absorption spectrometer, using a suitable standard set. The natural standard fused along with the sample set must be within 2 standard deviations of its known value or the whole set is re-assayed.

10% of the samples in a set are re-assayed and reported in duplicate, along with the standard and reagent blank.

Detection Limit:

Au – 0.01 g/tonne



8282 Sherbrooke Street,
Vancouver, B.C.
Canada V5X 4R6
Tel: 604 327-3436
Fax: 604 327-3423

Procedure Summary:

30 Element Aqua Regia Leach ICP-AES

Elements Analyzed:

Ag, Al, As, Ba, Be, Bi, Ca, Cd, Co, Cr, Cu, Fe, Hg, K, La, Mg, Mn, Mo, Na, Ni, P, Pb, S, Sb, Sc, Sr, Th, Ti, Tl, U, V, W, Zn, Zr

Procedure:

0.500 grams of the sample pulp is digested for 2 hours at 95°C with a 3:1 HCl:HNO₃ mixture. After cooling, the sample is diluted to 25mL with deionized water.

The solutions are analyzed by Inductively Coupled Plasma-Atomic Emission Spectra using standard operating conditions.

Each batch has 22 samples, 3 duplicates, one blank and two standards. Each batch will be rerun if the duplicates or the standards do not match the expected values.

Detection limit and analytical range are element specific.



8282 Sherbrooke Street,
Vancouver, B.C.
Canada V5X 4R6
Tel: 604 327-3436
Fax: 604 327-3423

Procedure Summary:

Metallic Gold Assay

Element(s) Analyzed:

Gold (Au) - g/tonne

Procedure:

The samples are pulverized to roughly 95% -150 mesh. Each sample is screened giving a +150 mesh fraction and a -150 mesh fraction.

The total weight of both fractions are recorded and both fractions are analyzed separately by Fire Assay for Au with total fusion on the +150 mesh fraction and duplicate fusions on the -150 mesh fraction.

The Net Au results are the combination of calculated values for both fractions.

Detection Limit : 0.01 g/tonne Au

Quality Assaying for over 25 Years

Assay Certificate

8V-2229-RA1

Company: **Ascot Resources Ltd**
Project: **Dilwor_**
Attn: **Sue Deane**

Jun-23-08

We hereby certify the following assay of 24 core samples submitted Jun-16-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
48701	0.03	0.02	2.4
48702	0.10		18.0
48703	0.01		1.6
48704	0.05		2.7
48705	0.05		2.0
48706	0.09		2.4
48707	<0.01		1.2
48708	0.01		0.9
48709	0.04		2.1
48710	0.11	0.11	3.0
48711	0.07		3.4
48712	0.02		1.5
48713	0.07		2.0
48714	0.27		3.5
48715	0.14		0.9
48716	0.23		3.2
48717	0.09		2.6
48718	0.51		22.1
48719	0.19		2.7
48720	0.01	<0.01	0.2
48721	1.68		181
48722	0.45		7.5
48723	<0.01		2.2
48724	0.03		3.2
*0218	0.89		
*BLANK	<0.01		

Au F.A. AA finish. Ag read from ICP solution

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2229-RA2

Company: **Ascot Resources Ltd**
Project: **Dilwor_**
Attn: **Sue Deane**

Jun-23-08

We hereby certify the following assay of 24 core samples submitted Jun-16-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
48725	0.03	0.05	1.7
48726	0.03		1.2
48727	0.14		4.4
48728	0.12		4.0
48729	0.17		3.3
48730	0.23		3.0
48731	0.02		2.1
48732	0.02		0.2
48733	0.01		<0.1
48734	0.06	0.06	0.3
48735	0.02		0.9
48736	0.04		0.5
48737	0.01		0.4
48738	0.03		0.8
48739	0.02		0.5
48740	0.06		1.8
48741	0.02		1.1
48742	<0.01		0.7
48743	0.02		0.8
48744	0.07	0.08	1.1
48745	0.01		1.0
48746	<0.01		<0.1
48747	1.26		232
48748	0.03		1.6
*0218	0.90		
*BLANK	<0.01		

Au F.A. AA finish. Ag read from ICP solution

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2229-RA3

Company: **Ascot Resources Ltd**
Project: **Dilwor_**
Attn: **Sue Deane**

Jun-23-08

We hereby certify the following assay of 15 core samples submitted Jun-16-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
48749	0.02	0.02	9.2
48750	0.01		3.8
48751	0.06		17.1
48752	0.01		2.4
48753	0.01		1.5
48754	<0.01		1.5
48755	<0.01		1.5
48756	0.01		1.5
48757	0.01		1.7
48758	0.01		1.4
48759	0.01		5.5
48760	<0.01		1.1
48761	<0.01		1.3
48762	0.01		1.0
48763	<0.01		0.7
*0218	0.88		
*BLANK	<0.01		

Au F.A. AA finish. Ag read from ICP solution

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2229RJ**

Date : Jun-23-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
48701	2.4	1.64	58	139	<0.5	11	0.77	2	12	20	<1	4.47	<1	0.18	<10	0.73	947	<2	0.01	6	980	<2	1.42	<5	2	21	<5	<0.01	<10	<10	33	<10	81	3
48702	18.0	1.52	91	124	<0.5	12	0.52	2	9	19	9	4.04	<1	0.19	<10	0.65	755	<2	0.01	3	944	37	1.35	<5	2	9	<5	<0.01	<10	<10	33	<10	162	2
48703	1.6	1.78	22	128	<0.5	11	0.59	1	10	21	<1	4.17	<1	0.18	10	0.78	990	<2	0.01	1	1028	<2	0.75	<5	2	13	<5	<0.01	<10	10	39	<10	87	3
48704	2.7	1.41	63	181	<0.5	5	0.66	1	11	21	1	3.79	1	0.18	<10	0.58	785	<2	0.01	2	938	4	1.26	5	2	17	<5	<0.01	<10	<10	29	<10	69	2
48705	2.0	1.58	44	104	<0.5	8	0.74	2	10	28	8	3.99	<1	0.16	10	0.67	955	<2	0.01	3	957	<2	0.93	<5	2	14	<5	<0.01	<10	10	36	<10	67	2
48706	2.4	1.37	85	147	<0.5	11	0.47	1	11	24	29	3.75	1	0.20	11	0.54	862	2	0.01	3	848	7	1.30	<5	2	7	5	<0.01	<10	11	25	<10	61	3
48707	1.2	1.79	18	142	<0.5	7	0.83	1	11	18	13	3.98	<1	0.20	14	0.67	943	<2	0.02	3	3284	<2	0.53	<5	2	18	<5	<0.01	<10	14	29	<10	73	3
48708	0.9	1.69	23	142	<0.5	7	0.36	1	11	17	<1	4.17	<1	0.20	<10	0.64	1012	<2	0.02	2	815	<2	0.90	<5	2	3	<5	<0.01	<10	<10	29	<10	80	2
48709	2.1	1.38	84	135	<0.5	11	0.37	2	9	37	3	4.03	<1	0.17	10	0.49	835	<2	0.02	3	606	2	1.50	<5	2	5	<5	<0.01	<10	10	23	<10	57	2
48710	3.0	1.74	94	145	<0.5	11	0.39	2	13	20	20	4.42	<1	0.21	11	0.69	1023	<2	0.02	4	1026	5	1.24	<5	2	5	<5	<0.01	<10	11	32	<10	87	3
48711	3.4	1.82	90	119	<0.5	11	0.63	2	13	21	15	4.63	<1	0.18	10	0.75	1199	<2	0.02	3	1375	<2	1.09	5	3	11	<5	<0.01	<10	10	45	<10	76	3
48712	1.5	2.28	11	130	<0.5	8	0.63	2	14	17	18	4.86	<1	0.19	<10	1.06	1626	<2	0.02	3	633	<2	0.34	<5	3	17	<5	<0.01	<10	<10	54	<10	79	3
48713	2.0	1.92	39	147	<0.5	13	0.45	2	12	26	7	4.62	<1	0.20	<10	0.86	1268	<2	0.02	2	661	3	1.02	<5	2	9	<5	<0.01	<10	<10	40	<10	71	3
48714	3.5	1.52	35	157	<0.5	7	0.67	2	10	27	3	3.90	<1	0.23	<10	0.59	1012	<2	0.01	2	477	15	1.14	<5	2	20	<5	<0.01	<10	<10	26	<10	84	3
48715	0.9	1.65	15	134	<0.5	6	0.72	1	10	30	<1	3.85	1	0.20	<10	0.65	1174	<2	0.01	3	559	<2	0.67	<5	2	21	<5	<0.01	<10	<10	30	<10	64	3
48716	3.2	1.00	105	140	<0.5	6	0.33	1	9	28	<1	3.25	1	0.22	<10	0.33	536	2	0.01	2	479	9	1.75	5	2	5	<5	<0.01	<10	<10	19	<10	47	3
48717	2.6	0.93	91	158	<0.5	10	0.62	1	10	49	<1	3.31	1	0.18	<10	0.33	628	3	0.01	3	566	16	1.85	<5	2	19	<5	<0.01	<10	<10	16	<10	51	2
48718	22.1	1.31	88	114	<0.5	13	2.63	6	14	48	9	4.83	<1	0.21	11	0.58	1354	<2	0.01	5	1111	304	2.76	5	3	103	<5	0.01	<10	11	26	<10	575	3
48719	2.7	1.85	120	126	<0.5	6	2.03	2	14	18	51	5.62	<1	0.20	11	0.87	1592	<2	0.01	4	1283	17	2.44	10	3	49	<5	0.03	<10	11	33	<10	153	3
48720	0.2	1.02	<5	235	<0.5	<5	0.50	1	6	119	<1	2.07	2	0.46	<10	0.60	565	2	0.06	5	725	<2	0.03	<5	2	43	5	0.13	<10	<10	39	<10	51	2
48721	181.5	0.88	217	210	<0.5	104	5.56	2	17	22	4196	3.77	5	0.17	<10	0.20	640	76	0.03	36	601	218	1.45	288	2	198	<5	0.06	<10	<10	23	27	254	9
48722	7.5	1.97	74	130	<0.5	14	5.10	2	15	15	42	5.03	<1	0.22	<10	1.03	2595	<2	0.01	3	1263	16	1.55	<5	3	143	<5	0.01	<10	10	33	<10	115	3
48723	2.2	2.29	60	166	<0.5	17	4.23	2	13	12	16	5.44	2	0.26	12	1.21	2416	<2	0.02	5	1378	<2	1.32	<5	4	127	<5	0.01	<10	12	36	<10	99	3
48724	3.2	1.73	58	134	<0.5	14	2.68	2	15	20	31	5.30	<1	0.23	<10	0.90	1539	<2	0.01	3	1417	7	2.65	8	3	83	<5	<0.01	<10	<10	27	<10	91	3
48725	1.7	2.14	63	197	<0.5	<5	2.75	1	17	9	13	4.66	<1	0.27	13	1.18	1849	<2	0.02	6	1293	6	1.08	<5	4	94	<5	<0.01	<10	<10	39	<10	100	3
48726	1.2	1.61	48	176	<0.5	<5	2.38	1	13	12	<1	3.44	<1	0.27	11	0.83	1390	<2	0.02	5	1152	7	0.80	<5	3	72	<5	<0.01	<10	<10	28	<10	66	2
48727	4.4	1.75	93	148	<0.5	<5	1.88	1	16	9	28	4.86	<1	0.29	12	0.89	1413	<2	0.02	6	1244	9	2.13	<5	3	66	<5	<0.01	<10	<10	33	<10	86	3
48728	4.0	1.52	93	131	<0.5	<5	1.56	1	16	12	23	4.76	<1	0.29	11	0.73	1229	<2	0.02	5	1030	10	2.56	<5	2	56	<5	0.01	<10	<10	28	<10	65	3
48729	3.3	1.42	96	126	<0.5	<5	1.14	1	14	10	24	4.37	<1	0.36	<10	0.65	1013	<2	0.02	4	1236	19	2.37	<5	3	50	<5	<0.01	<10	<10	26	<10	71	3
48730	3.0	1.41	85	193	<0.5	<5	1.69	1	13	8	12	3.49	<1	0.30	<10	0.66	1051	<2	0.02	4	1168	8	1.26	<5	2	61	<5	<0.01	<10	<10	20	<10	70	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2229RJ

Date : Jun-23-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
48731	2.1	1.33	86	145	<0.5	<5	2.41	1	14	6	11	4.21	<1	0.33	<10	0.58	1165	<2	0.02	4	1140	10	2.45	<5	2	106	5	<0.01	<10	<10	20	<10	53	3
48732	0.2	1.64	26	176	<0.5	<5	2.70	1	11	9	1	3.88	<1	0.31	10	0.73	1567	<2	0.03	4	1168	5	1.05	<5	2	99	5	<0.01	<10	<10	24	<10	64	2
48733	<0.2	2.33	<5	182	<0.5	<5	2.46	1	12	6	9	4.61	<1	0.32	14	1.05	1981	<2	0.02	4	1258	<2	0.07	<5	3	81	5	<0.01	<10	<10	33	<10	93	3
48734	0.3	1.92	7	144	<0.5	<5	2.89	1	12	9	13	4.21	<1	0.26	11	0.86	2000	<2	0.02	4	1101	5	0.52	<5	2	97	5	0.01	<10	<10	31	<10	76	3
48735	0.9	1.66	68	167	<0.5	<5	2.27	1	13	5	11	3.76	<1	0.29	10	0.71	1527	<2	0.02	4	1123	5	0.81	<5	2	66	<5	0.01	<10	<10	24	<10	70	2
48736	0.5	1.95	8	143	<0.5	<5	3.36	1	14	7	9	4.33	<1	0.26	12	0.83	2027	<2	0.02	4	1103	4	0.51	<5	2	96	<5	0.05	<10	<10	30	<10	83	3
48737	0.4	2.07	25	196	<0.5	<5	4.04	1	14	7	5	4.63	<1	0.31	13	0.81	2192	<2	0.02	5	1103	2	0.76	<5	3	103	7	0.07	<10	<10	38	<10	66	3
48738	0.8	1.99	26	167	<0.5	<5	2.35	1	15	7	12	4.66	<1	0.27	10	0.82	1890	<2	0.02	4	1125	5	0.81	<5	3	66	<5	0.06	<10	<10	33	<10	79	3
48739	0.5	1.83	9	162	0.5	<5	2.64	1	13	5	9	3.95	<1	0.28	10	0.75	1825	<2	0.02	3	1186	4	0.59	<5	2	75	<5	0.08	<10	<10	29	<10	71	3
48740	1.8	2.02	66	157	<0.5	<5	2.06	2	18	8	18	5.10	<1	0.29	11	0.93	2039	<2	0.02	5	1291	9	1.48	<5	3	59	<5	0.02	<10	<10	39	<10	82	3
48741	1.1	1.85	28	166	<0.5	<5	0.44	1	15	7	8	4.78	<1	0.29	10	0.78	1370	<2	0.02	4	1161	7	1.60	<5	3	20	<5	0.01	<10	<10	36	<10	70	3
48742	0.7	2.06	17	132	<0.5	<5	1.36	1	16	10	15	4.66	<1	0.22	11	0.95	1828	<2	0.02	5	1161	<2	0.72	<5	3	46	<5	0.02	<10	<10	43	<10	79	3
48743	0.8	1.70	16	129	<0.5	<5	2.78	1	16	7	4	5.21	1	0.28	12	0.78	1795	<2	0.02	5	1190	7	2.64	<5	3	85	<5	0.04	<10	<10	36	<10	73	3
48744	1.1	1.02	50	172	<0.5	<5	2.78	1	13	11	5	3.75	<1	0.27	<10	0.40	1303	<2	0.02	3	853	13	2.53	<5	2	124	6	0.03	<10	<10	21	<10	48	3
48745	1.0	1.46	30	116	<0.5	<5	2.14	1	16	8	8	4.70	<1	0.27	10	0.72	1319	<2	0.02	5	1135	9	2.64	<5	2	79	<5	0.03	<10	<10	28	<10	90	3
48746	<0.2	1.01	<5	226	<0.5	<5	0.51	<1	7	69	<1	1.92	<1	0.50	<10	0.59	544	<2	0.07	5	702	4	0.01	<5	2	57	<5	0.13	<10	<10	38	<10	40	2
48747	>200.0	0.91	1850	93	<0.5	62	4.57	2	58	23	2410	3.14	2	0.09	10	0.25	889	132	0.06	23	856	383	0.65	400	2	141	7	0.04	<10	<10	24	25	288	8
48748	1.6	1.92	39	163	<0.5	<5	1.41	1	14	17	13	4.51	<1	0.27	10	0.94	1455	<2	0.02	5	1092	6	1.24	<5	2	46	<5	0.01	<10	<10	38	<10	73	3
48749	9.2	1.38	44	117	<0.5	10	2.51	2	14	22	26	4.66	1	0.29	<10	0.82	1434	<2	0.02	11	1245	23	3.13	<5	2	98	<5	0.02	<10	<10	30	<10	94	3
48750	3.8	1.19	30	88	<0.5	10	3.61	2	15	17	26	4.89	1	0.30	10	0.62	1612	<2	0.02	3	1205	14	3.94	<5	2	101	<5	0.03	<10	10	24	<10	76	3
48751	17.1	1.05	78	87	<0.5	10	3.40	4	14	18	32	5.09	1	0.29	10	0.53	1555	<2	0.01	3	1278	48	4.48	7	2	99	<5	0.03	<10	10	22	<10	397	3
48752	2.4	2.15	33	167	<0.5	13	2.79	2	13	9	25	5.08	<1	0.33	12	1.07	1897	<2	0.02	4	1284	10	1.62	6	3	84	<5	0.02	<10	12	40	<10	83	3
48753	1.5	2.27	19	415	<0.5	13	2.93	1	13	7	31	4.63	<1	0.28	15	1.18	1957	<2	0.02	3	1234	3	0.47	<5	3	76	<5	<0.01	<10	15	42	<10	84	3
48754	1.5	2.41	22	156	<0.5	13	2.88	2	13	5	31	4.98	<1	0.28	12	1.29	2034	<2	0.02	4	1422	3	0.53	<5	4	80	<5	0.01	<10	12	42	<10	95	3
48755	1.5	2.14	27	180	<0.5	12	2.62	2	12	8	30	4.86	<1	0.28	15	1.02	1866	<2	0.02	3	1196	7	0.96	<5	3	76	<5	0.01	<10	15	41	<10	87	3
48756	1.5	2.16	13	159	<0.5	13	3.54	2	11	7	23	4.68	<1	0.30	12	1.05	2272	<2	0.02	2	1239	9	0.60	5	3	117	<5	0.02	<10	12	36	<10	87	3
48757	1.7	1.75	9	140	<0.5	10	3.98	1	9	9	26	4.60	<1	0.30	11	0.80	1908	<2	0.03	2	1289	13	1.77	<5	2	106	<5	0.01	<10	11	33	<10	83	3
48758	1.4	1.79	14	127	<0.5	11	3.70	1	9	15	24	4.31	1	0.28	10	0.88	2225	<2	0.03	2	1226	9	1.16	<5	2	110	<5	0.01	<10	11	29	<10	85	2
48759	5.5	1.84	23	128	<0.5	10	3.58	1	10	7	23	4.17	<1	0.28	10	0.88	2393	<2	0.03	1	1140	15	0.92	5	2	111	<5	0.01	<10	10	31	<10	100	3
48760	1.1	2.02	<5	123	<0.5	10	2.90	1	12	5	30	4.49	<1	0.27	<10	0.94	2304	<2	0.03	2	1233	6	0.76	<5	2	88	<5	0.01	<10	<10	36	<10	88	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth

Sample type:

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2229RJ

Date : Jun-23-08

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
48761	1.3	1.47	6	137	<0.5	9	3.44	1	12	5	32	4.33	<1	0.30	<10	0.65	1875	<2	0.03	1	1171	7	2.09	<5	2	100	<5	0.01	<10	<10	27	<10	76	3
48762	1.0	1.32	9	143	<0.5	9	5.24	2	11	5	35	4.42	<1	0.31	10	0.56	2242	<2	0.02	2	1248	14	2.60	5	2	199	<5	<0.01	<10	10	23	<10	73	3
48763	0.7	1.88	8	193	<0.5	10	2.34	1	10	4	28	4.18	<1	0.34	<10	0.78	1784	<2	0.03	1	1302	3	0.74	<5	2	73	<5	0.02	<10	<10	32	<10	82	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 35 Years

Assay Certificate


8V-2237-RA1

Company: **Ascot Resources**
 Project:
 Attn: **Rick Kasum**

Jun-17-08

We hereby certify the following assay of 2 rock samples submitted Jun-02-08

Sample Name	Au g/tonne	Ag g/tonne	Cu %	Pb %	Zn %
TOP	3.43	2073	0.030	1.10	1.05
Bottom	3.57	1488	0.082	0.63	1.40
*DUP TOP	3.03	2081	0.029	1.10	1.04
*0218	0.91				
*CCu-1c		131.0		0.35	3.95
*CZn-3			0.687		
*BLANK	<0.01	<0.1	<0.001	<0.01	<0.01

Certified by _____ 



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2278-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth**
Attn: **Sue Deane**

Jul-04-08

We hereby certify the following assay of 24 core samples submitted Jun-19-08

Sample Name	Au g/tonne	Au-Check g/tonne
48764	<0.01	0.02
48765	<0.01	
48766	0.01	
48767	<0.01	
48768	0.01	
48769	0.02	
48770	<0.01	
48771	<0.01	
48772	0.01	
48773	0.05	0.03
48774	0.10	
48775	0.01	
48776	<0.01	
48777	1.79	
48778	0.06	
48779	0.03	
48780	0.01	
48781	0.02	
48782	0.03	
48783	0.03	0.03
48784	0.03	
48785	0.01	
48786	0.01	
48787	0.01	
*0218	0.93	
*BLANK	<0.01	

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2278-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth**
Attn: **Sue Deane**

Jul-04-08

We hereby certify the following assay of 24 core samples submitted Jun-19-08

Sample Name	Au g/tonne	Au-Check g/tonne
48788	0.01	0.01
48789	<0.01	
48790	0.01	
48791	<0.01	
48792	0.01	
48793	<0.01	
48794	0.01	
48795	0.01	
48796	<0.01	
48797	0.02	0.01
48798	0.01	
48799	0.09	
48800	<0.01	
48801	0.03	
48802	0.02	
48803	0.02	
48804	0.02	
48805	0.02	
48806	0.02	
48807	0.01	<0.01
48808	0.02	
48809	0.03	
48810	0.03	
48811	0.01	
*0218	0.91	
*BLANK	<0.01	

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2278-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth**
Attn: **Sue Deane**

Jul-04-08

We hereby certify the following assay of 24 core samples submitted Jun-19-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
48812	1.24	1.31	234.3
48813	0.01		
48814	0.19		
48815	0.04		
48816	0.07		
48817	0.04		
48818	0.01		
48819	0.01		
48820	0.01		
48821	0.05	0.04	
48822	0.02		
48823	0.05		
48824	0.42		
48825	0.17		
48826	0.14		
48827	0.02		
48828	<0.01		
48829	0.01		
48830	0.01		
48831	0.01	0.01	
48832	0.02		
48833	0.61		
48834	0.02		
48835	0.02		
*0218	0.86		
*CCu-1c			128.8
*BLANK	<0.01		<0.1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2278-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth**
Attn: **Sue Deane**

Jul-04-08

We hereby certify the following assay of 24 core samples submitted Jun-19-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
48836	0.10	0.10		
48837	0.07			
48838	0.02			
48839	0.13			
48840	0.02			
48841	0.28			
48842	0.02			
48843	0.25			
48844	0.04			
48845	0.08	0.08		
48846	0.05			
48847	0.14			
48848	0.10			
48849	0.26			
48850	0.16			
48851	0.05			
48852	0.74			
48853	0.32			
48854	0.40			
48855	0.34	0.31		
48856	5.72		1162	2.81
48857	1.61		1073	1.57
48858	0.24			
48859	0.75			
*0218	0.88			
*CCu-1c			131.7	4.00
*BLANK	<0.01		<0.1	<0.01

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2278-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth**
Attn: **Sue Deane**

Jul-04-08

We hereby certify the following assay of 24 core samples submitted Jun-19-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
48860	0.02	<0.01	
48861	1.43		236.9
48862	0.26		
48863	0.47		
48864	0.69		
48865	0.43		
48866	0.26		
48867	0.43		
48868	0.39		
48869	0.37	0.36	
48870	0.17		
48871	0.51		
48872	0.21		
48873	0.28		
48874	0.24		
48875	0.15		
48876	0.58		
48877	0.85		
48878	0.77		
48879	0.54	0.52	
48880	0.34		
48881	0.27		
48882	0.18		
48883	0.32		
*0218	0.88		
*CCu-1c			131.7
*BLANK	<0.01		<0.1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2278-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth**
Attn: **Sue Deane**

Jul-04-08

We hereby certify the following assay of 24 core samples submitted Jun-19-08

Sample Name	Au g/tonne	Au-Check g/tonne
48884	0.31	0.36
48885	0.15	
48886	0.71	
48887	0.23	
48888	0.20	
48889	0.22	
48890	0.24	
48891	0.19	
48892	0.22	
48893	0.22	0.20
48894	0.16	
48895	0.21	
48896	0.23	
48897	0.22	
48898	0.24	
48899	0.30	
48900	0.55	
48901	0.61	
48902	0.42	
48903	1.43	1.28
48904	1.47	
48905	0.51	
48906	0.21	
48907	0.33	
*0218	0.94	
*BLANK	<0.01	

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2278-RA7

Company: **Ascot Resources Ltd**
Project: **Dilworth**
Attn: **Sue Deane**

Jul-04-08

We hereby certify the following assay of 13 core samples submitted Jun-19-08

Sample Name	Au g/tonne	Au-Check g/tonne
48908	0.21	0.22
48909	0.12	
48910	0.11	
48911	0.13	
48912	0.10	
48913	0.08	
48914	0.09	
48915	0.16	
48916	0.10	
48917	0.09	0.09
48918	0.16	
48919	0.15	
48920	0.15	
*0218	0.86	
*BLANK	<0.01	

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2278RJ**

Date : Jul-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
48764	0.6	1.43	38	167	<0.5	9	2.13	1	13	6	34	3.24	<1	0.31	<10	0.59	1509	<2	0.03	1	1205	9	0.48	<5	2	70	<5	0.01	<10	<10	23	<10	61	2
48765	0.3	1.55	<5	171	<0.5	9	3.24	1	13	7	27	3.42	<1	0.29	<10	0.66	1955	<2	0.02	2	1160	2	0.16	<5	2	117	<5	0.01	<10	<10	21	<10	66	2
48766	0.5	1.41	5	161	<0.5	8	2.84	1	16	4	27	3.25	<1	0.29	<10	0.60	1761	<2	0.01	1	1165	5	0.37	<5	2	105	<5	0.01	<10	<10	18	<10	68	2
48767	1.0	1.43	<5	161	<0.5	<5	2.84	1	13	6	42	3.18	<1	0.29	<10	0.64	1969	<2	0.01	3	1005	4	0.34	<5	2	116	<5	0.01	<10	<10	22	<10	66	2
48768	2.2	2.09	21	122	<0.5	11	2.10	2	23	<1	106	5.21	<1	0.23	<10	1.14	2377	<2	0.01	5	1133	8	1.27	<5	3	81	<5	0.01	<10	<10	58	<10	84	3
48769	4.3	1.84	24	127	<0.5	9	3.87	2	25	3	93	4.98	<1	0.24	<10	1.00	2905	<2	0.02	5	1004	15	1.66	5	3	124	<5	0.01	<10	<10	53	<10	76	3
48770	2.0	2.06	6	127	<0.5	10	2.95	2	34	2	111	5.20	<1	0.24	<10	1.13	2850	<2	0.02	5	1076	9	1.35	<5	3	95	<5	0.01	<10	<10	63	<10	81	3
48771	1.5	2.06	10	125	<0.5	10	3.67	2	22	1	80	4.32	<1	0.24	<10	1.14	3122	<2	0.02	4	951	4	0.27	<5	3	101	<5	0.01	<10	<10	55	<10	73	2
48772	1.7	2.20	8	127	<0.5	9	2.25	2	32	1	103	4.82	<1	0.22	<10	1.23	2820	<2	0.02	5	1189	3	0.39	7	3	65	<5	0.01	<10	<10	63	<10	88	3
48773	2.6	1.18	117	76	<0.5	7	0.96	2	28	8	51	5.07	<1	0.23	<10	0.55	1309	<2	0.01	4	803	14	3.46	<5	2	38	<5	0.01	<10	<10	34	<10	46	3
48774	5.6	2.45	282	37	<0.5	18	1.33	5	25	14	87	10.78	<1	0.11	<10	1.20	3129	<2	0.01	4	752	35	>5.00	8	3	61	<5	0.01	<10	<10	129	<10	74	6
48775	2.8	1.84	84	148	<0.5	9	2.96	2	23	2	84	4.63	<1	0.26	<10	0.96	2431	<2	0.01	4	1069	5	1.08	7	3	81	<5	0.02	<10	<10	45	<10	63	3
48776	<0.2	0.81	<5	197	<0.5	<5	0.35	<1	5	89	1	1.72	<1	0.43	<10	0.52	475	<2	0.06	6	715	<2	0.01	<5	2	33	5	0.10	<10	<10	31	<10	39	2
48777	144.5	0.51	200	124	<0.5	87	3.45	2	14	15	3420	2.47	3	0.13	<10	0.16	408	72	0.02	29	550	194	1.10	271	1	139	<5	0.03	<10	<10	14	26	204	5
48778	12.7	2.00	72	128	<0.5	14	3.43	2	20	11	88	4.77	<1	0.23	<10	1.15	2770	<2	0.01	4	959	68	0.92	<5	3	88	<5	0.02	<10	<10	52	<10	94	3
48779	2.1	2.02	8	135	<0.5	7	3.40	2	18	6	96	4.21	<1	0.24	<10	1.27	2553	<2	0.02	3	1123	18	0.35	<5	3	108	<5	0.02	<10	<10	54	<10	69	2
48780	2.2	2.03	16	132	<0.5	11	3.03	2	17	7	83	4.48	<1	0.25	<10	1.32	2702	<2	0.02	3	1060	10	0.70	<5	3	104	<5	0.02	<10	<10	53	<10	67	2
48781	2.2	1.79	30	122	<0.5	10	2.72	1	18	3	96	3.79	<1	0.24	<10	1.21	2576	<2	0.02	4	1074	6	0.56	<5	3	83	<5	0.01	<10	<10	49	<10	72	2
48782	2.3	1.76	55	207	<0.5	10	3.21	2	19	23	33	4.39	<1	0.23	14	1.33	2048	<2	0.02	7	1778	23	0.90	<5	4	137	<5	<0.01	<10	14	54	<10	126	3
48783	8.1	1.92	49	126	<0.5	11	1.67	2	30	5	100	5.04	<1	0.26	<10	1.12	2832	<2	0.01	5	1314	10	1.44	<5	3	83	<5	<0.01	<10	<10	45	<10	81	3
48784	3.4	1.67	45	158	<0.5	9	1.48	2	23	6	69	4.50	<1	0.27	<10	0.76	2305	<2	0.01	1	1488	6	0.75	6	3	64	<5	0.01	<10	<10	36	<10	79	3
48785	1.9	1.42	38	211	<0.5	9	1.71	1	22	3	33	4.10	<1	0.28	<10	0.61	2025	<2	0.02	2	1770	6	0.70	6	3	86	<5	0.01	<10	<10	32	<10	70	3
48786	0.6	1.28	7	424	<0.5	8	1.69	1	22	5	21	3.57	<1	0.29	<10	0.54	2017	<2	0.01	1	1753	2	0.10	6	3	92	<5	0.01	<10	<10	32	<10	61	3
48787	1.1	1.26	72	266	<0.5	8	1.37	1	27	3	62	3.77	<1	0.30	<10	0.54	1766	<2	0.01	2	1496	2	0.45	6	3	74	<5	0.01	<10	<10	36	<10	66	3
48788	0.7	1.45	<5	596	<0.5	8	2.14	2	27	2	64	4.52	1	0.30	<10	0.61	1875	<2	0.02	4	1424	11	0.05	7	3	117	<5	0.03	<10	<10	53	<10	84	4
48789	1.1	1.45	<5	459	<0.5	<5	2.00	2	24	2	89	4.33	<1	0.24	<10	0.64	1836	<2	0.01	3	1408	8	0.08	7	3	90	<5	0.02	<10	<10	42	<10	82	3
48790	2.4	1.31	53	322	<0.5	<5	1.17	1	25	<1	43	3.40	<1	0.25	<10	0.57	1122	<2	0.01	4	1498	8	0.50	<5	3	64	<5	<0.01	<10	<10	30	<10	74	2
48791	3.3	1.77	32	172	<0.5	7	2.36	2	23	1	94	4.14	<1	0.25	<10	0.88	1865	<2	0.01	4	1535	8	0.41	8	3	104	<5	<0.01	<10	<10	37	<10	74	2
48792	2.8	2.08	<5	159	<0.5	6	3.27	2	22	1	260	4.64	<1	0.25	<10	1.21	2353	<2	0.01	6	1401	9	0.06	<5	5	144	<5	<0.01	<10	<10	42	<10	71	3
48793	1.7	2.34	<5	133	<0.5	7	2.52	2	24	2	50	5.56	<1	0.27	10	1.63	2217	<2	0.01	9	1666	11	0.02	<5	5	123	<5	<0.01	<10	10	49	<10	104	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2278RJ

Date : Jul-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
48794	3.1	2.54	<5	122	<0.5	8	6.06	2	25	1	113	5.59	1	0.26	<10	1.49	3479	<2	0.01	7	1492	10	0.24	6	5	545	<5	<0.01	<10	<10	51	<10	135	3
48795	4.4	1.64	82	161	<0.5	5	3.32	2	25	6	79	4.48	<1	0.27	<10	0.84	2083	<2	0.01	5	1528	11	0.98	<5	4	238	<5	<0.01	<10	<10	33	<10	91	3
48796	2.2	1.91	6	520	0.5	<5	2.59	2	16	15	86	4.33	<1	0.24	14	1.10	1430	<2	0.02	5	1761	30	0.19	<5	3	199	<5	<0.01	<10	14	43	<10	144	3
48797	3.7	1.83	198	124	<0.5	9	1.42	3	31	5	95	5.12	2	0.24	<10	1.01	1666	<2	0.01	6	1546	40	1.60	7	3	73	<5	<0.01	<10	<10	45	<10	123	3
48798	2.3	1.68	64	119	<0.5	8	2.66	2	20	6	55	4.28	<1	0.22	<10	1.00	2387	<2	0.01	5	1662	13	0.84	5	3	172	<5	<0.01	<10	<10	34	<10	80	2
48799	4.6	1.15	172	111	<0.5	8	2.98	2	22	6	128	5.04	<1	0.25	<10	0.97	2214	<2	0.01	3	1548	18	2.10	7	4	155	<5	<0.01	<10	<10	30	<10	70	3
48800	2.7	1.14	148	121	<0.5	<5	4.41	2	19	15	65	3.84	<1	0.24	<10	0.81	2543	<2	0.02	3	1411	13	1.37	7	4	241	<5	<0.01	<10	<10	30	<10	57	2
48801	2.1	1.57	160	113	<0.5	6	3.51	2	27	4	37	4.51	<1	0.24	<10	0.95	2191	<2	0.01	5	1587	14	1.49	<5	3	126	<5	<0.01	<10	<10	41	<10	73	3
48802	2.9	2.63	27	99	<0.5	10	3.39	2	26	4	135	5.78	<1	0.20	<10	1.78	2993	<2	0.01	13	1485	12	0.78	<5	4	164	<5	<0.01	<10	<10	55	<10	95	3
48803	3.7	2.51	37	120	<0.5	7	3.88	2	23	5	97	5.77	<1	0.24	<10	1.52	2691	<2	0.01	6	1453	17	0.90	6	3	158	<5	<0.01	<10	<10	58	<10	87	3
48804	4.3	2.37	20	115	<0.5	6	4.46	2	23	6	93	5.45	<1	0.25	<10	1.20	2554	<2	0.01	5	1618	11	0.77	6	4	168	<5	<0.01	<10	<10	59	<10	78	3
48805	3.2	2.05	39	104	<0.5	7	6.26	3	27	4	92	5.57	<1	0.24	<10	0.92	2534	2	0.01	6	1518	10	1.30	9	4	201	<5	<0.01	<10	<10	52	<10	72	3
48806	3.6	2.59	40	120	<0.5	13	6.02	3	27	4	79	6.12	<1	0.21	<10	1.55	2872	<2	0.01	7	1450	19	1.33	11	5	181	<5	<0.01	<10	<10	70	<10	80	4
48807	2.5	2.55	15	131	<0.5	12	5.15	2	25	5	80	5.95	<1	0.19	<10	1.72	2774	<2	0.02	5	1439	13	1.36	6	5	172	<5	0.01	<10	<10	77	<10	83	3
48808	3.5	2.23	24	124	<0.5	6	5.63	3	29	4	70	5.87	<1	0.19	<10	1.31	2929	<2	0.02	6	1453	30	1.57	5	5	184	<5	<0.01	<10	<10	71	<10	109	3
48809	3.9	2.29	35	164	<0.5	10	5.38	3	31	6	216	5.70	<1	0.20	<10	1.29	2861	<2	0.02	6	1373	16	1.38	6	5	157	<5	<0.01	<10	<10	75	<10	79	3
48810	3.0	2.52	14	105	<0.5	8	4.95	3	28	5	68	6.00	<1	0.17	<10	1.46	2839	<2	0.02	6	1494	9	0.96	<5	6	150	<5	0.01	<10	<10	85	<10	93	4
48811	<0.2	0.87	<5	219	<0.5	<5	0.39	1	6	62	<1	1.88	1	0.43	<10	0.56	530	<2	0.05	6	755	7	0.02	<5	2	38	<5	0.11	<10	<10	35	<10	45	2
48812	>200.0	0.60	2046	79	<0.5	56	3.59	2	53	18	2196	2.62	2	0.06	<10	0.21	700	132	0.04	20	785	365	0.60	508	1	132	<5	0.02	<10	<10	14	21	275	5
48813	2.4	2.69	18	161	<0.5	12	4.94	3	32	8	76	6.10	<1	0.22	<10	1.48	3016	<2	0.02	7	1411	10	0.89	<5	6	148	<5	0.01	<10	<10	86	<10	88	4
48814	66.2	1.30	334	65	<0.5	<5	3.01	4	23	20	46	5.91	<1	0.21	<10	0.71	1790	<2	0.01	5	1025	149	4.21	15	3	105	<5	<0.01	<10	<10	42	<10	276	3
48815	7.3	2.24	87	104	<0.5	8	4.00	2	28	6	63	5.75	<1	0.22	<10	1.35	2492	<2	0.02	5	1353	18	1.74	<5	5	111	<5	<0.01	<10	<10	72	<10	82	3
48816	4.3	2.34	62	110	<0.5	12	4.30	2	29	6	75	6.05	<1	0.23	<10	1.36	2523	<2	0.02	5	1420	14	1.81	<5	5	118	<5	<0.01	<10	<10	74	<10	72	3
48817	2.7	2.02	105	92	<0.5	7	4.71	3	25	5	65	6.16	<1	0.20	<10	1.25	2305	<2	0.01	5	1198	17	2.75	<5	5	116	<5	<0.01	<10	<10	65	<10	65	4
48818	2.2	2.69	19	135	<0.5	9	4.88	2	24	4	86	5.60	<1	0.24	<10	1.70	2402	<2	0.01	5	1346	5	0.42	<5	6	143	<5	<0.01	<10	<10	77	<10	85	3
48819	2.1	2.30	19	122	<0.5	7	4.43	2	25	4	58	5.36	<1	0.26	<10	1.39	2033	<2	0.01	5	1297	9	1.05	<5	5	125	<5	<0.01	<10	<10	68	<10	68	3
48820	2.0	2.92	21	109	<0.5	8	4.55	3	23	4	72	6.13	<1	0.21	<10	1.92	2399	<2	0.01	5	1371	10	0.90	<5	6	122	<5	<0.01	<10	<10	80	<10	92	3
48821	1.9	1.91	70	101	<0.5	6	5.83	2	22	8	50	5.67	<1	0.22	<10	1.27	2136	<2	0.01	4	1192	15	2.69	<5	5	161	<5	<0.01	<10	<10	52	<10	66	3
48822	1.6	2.47	39	103	<0.5	9	5.04	2	24	3	62	5.95	<1	0.22	<10	1.57	2052	<2	0.01	6	1383	11	1.46	<5	5	142	<5	<0.01	<10	<10	75	<10	77	3
48823	2.4	1.67	104	98	<0.5	6	4.95	2	21	7	59	5.47	1	0.24	<10	0.95	1589	<2	0.02	4	1209	15	2.67	<5	4	159	<5	<0.01	<10	<10	51	<10	66	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2278RJ

Date : Jul-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
48824	3.2	1.74	137	89	<0.5	7	5.20	2	20	4	53	5.67	<1	0.21	<10	1.02	1822	<2	0.02	4	1215	18	2.67	<5	4	154	<5	<0.01	<10	<10	54	<10	71	3
48825	7.1	2.06	129	95	<0.5	11	5.10	3	20	4	76	5.72	<1	0.21	<10	1.24	1975	<2	0.01	4	1348	93	2.11	<5	5	159	<5	<0.01	<10	<10	62	<10	144	3
48826	37.0	1.17	268	87	<0.5	5	4.24	3	16	13	93	4.75	<1	0.22	<10	0.67	1580	<2	0.01	3	964	111	3.23	7	3	126	<5	<0.01	<10	<10	34	<10	201	3
48827	3.1	2.67	79	104	<0.5	13	4.75	2	26	4	61	6.08	<1	0.23	<10	1.83	2700	<2	0.01	5	1422	16	1.59	<5	6	140	<5	<0.01	<10	<10	75	<10	94	3
48828	2.8	2.74	33	106	<0.5	5	4.12	2	27	6	102	6.13	<1	0.25	<10	1.77	2408	<2	0.02	6	1505	10	1.24	<5	5	140	<5	<0.01	<10	<10	84	<10	95	3
48829	1.6	2.82	33	99	<0.5	7	4.93	2	27	2	81	6.17	<1	0.21	<10	1.84	2105	<2	0.02	7	1463	9	1.03	<5	5	171	<5	<0.01	<10	<10	83	<10	93	3
48830	1.6	2.44	28	91	<0.5	7	6.43	2	25	3	95	5.87	<1	0.21	<10	1.52	2295	<2	0.01	5	1458	12	1.49	<5	5	172	<5	0.01	<10	<10	67	<10	84	3
48831	1.6	2.58	37	88	<0.5	9	6.35	2	27	4	79	6.05	<1	0.21	<10	1.59	2342	<2	0.01	5	1467	9	1.32	<5	5	167	<5	0.01	<10	<10	72	<10	86	3
48832	1.4	2.17	36	104	<0.5	7	5.41	2	25	5	82	6.00	<1	0.26	<10	1.33	1845	<2	0.01	5	1380	12	2.38	<5	4	162	<5	0.01	<10	<10	57	<10	82	3
48833	2.5	1.42	107	88	<0.5	5	5.58	2	19	13	61	4.53	1	0.23	<10	0.77	1727	<2	0.01	4	1085	30	2.22	5	3	171	<5	<0.01	<10	<10	37	<10	55	3
48834	1.6	1.81	48	82	<0.5	5	5.02	2	21	11	38	4.85	<1	0.20	<10	0.99	1961	<2	0.02	4	1094	15	1.54	<5	3	125	<5	0.01	<10	<10	53	<10	56	3
48835	1.7	1.95	53	91	<0.5	6	4.60	2	19	11	36	4.50	<1	0.20	<10	1.20	2204	<2	0.01	1	1219	16	0.88	<5	3	117	<5	0.01	<10	<10	58	<10	71	2
48836	2.5	1.43	190	109	<0.5	5	4.65	2	21	11	43	4.49	<1	0.24	<10	0.78	1834	<2	0.01	2	1228	24	2.07	<5	3	137	<5	0.01	<10	<10	43	<10	108	2
48837	2.5	1.87	219	95	<0.5	8	6.03	2	22	<1	50	4.79	<1	0.24	<10	1.06	2293	<2	0.01	2	1346	35	1.49	7	3	155	<5	<0.01	<10	<10	58	<10	117	2
48838	2.8	1.71	99	100	0.5	8	7.77	2	22	<1	46	4.32	<1	0.26	<10	0.84	2492	<2	0.01	2	1597	18	0.97	<5	4	204	<5	<0.01	<10	<10	65	<10	59	2
48839	54.1	1.98	152	96	<0.5	9	6.49	4	23	2	76	5.56	<1	0.22	<10	1.13	2600	<2	0.01	3	1250	222	1.99	16	3	162	<5	<0.01	<10	<10	62	<10	246	3
48840	2.7	2.04	72	87	<0.5	9	5.90	3	23	1	40	4.90	<1	0.20	<10	1.11	2529	<2	0.01	1	1656	39	0.88	5	3	154	<5	<0.01	<10	<10	60	<10	199	3
48841	5.1	2.05	63	100	<0.5	8	4.10	4	21	<1	64	5.17	<1	0.24	<10	1.16	2018	<2	0.01	1	1494	96	1.11	5	3	111	<5	<0.01	<10	<10	58	<10	415	3
48842	1.7	2.02	91	100	<0.5	9	4.74	2	23	2	55	5.35	<1	0.22	<10	1.07	1824	<2	0.01	3	1394	24	1.47	6	3	140	<5	<0.01	<10	<10	69	<10	78	3
48843	4.2	0.43	305	95	<0.5	5	0.32	3	11	12	48	3.48	<1	0.21	<10	0.10	318	5	0.01	2	948	87	2.41	10	1	19	<5	<0.01	<10	<10	11	<10	258	2
48844	2.8	0.64	72	97	<0.5	6	0.30	2	11	6	116	3.48	<1	0.24	<10	0.31	594	7	0.01	2	1124	28	2.07	7	1	12	<5	<0.01	<10	<10	18	<10	226	2
48845	2.1	0.73	105	96	<0.5	5	0.30	2	12	8	71	4.12	1	0.25	<10	0.33	517	5	0.01	2	1137	20	2.97	7	1	13	<5	<0.01	<10	<10	19	<10	63	2
48846	1.7	1.14	62	120	<0.5	11	0.41	2	12	8	56	4.08	<1	0.26	10	0.56	899	10	0.01	2	1162	19	2.03	6	2	26	<5	<0.01	<10	10	33	<10	130	2
48847	1.1	1.65	35	143	<0.5	7	0.47	3	13	7	64	4.11	<1	0.28	10	0.89	1341	5	0.01	2	1287	106	0.72	10	2	29	<5	<0.01	<10	10	51	<10	213	2
48848	1.8	1.76	47	146	<0.5	<5	0.64	8	13	10	98	4.35	<1	0.28	12	1.04	1513	7	0.01	3	1249	48	0.70	6	3	48	<5	<0.01	<10	12	52	<10	697	3
48849	3.0	1.84	141	128	<0.5	8	1.03	3	15	6	174	4.85	<1	0.26	10	1.04	1595	13	0.02	3	1274	49	1.10	5	3	68	<5	<0.01	<10	10	63	<10	210	3
48850	6.2	1.27	156	115	<0.5	5	0.46	4	13	9	90	4.44	<1	0.26	10	0.69	1094	9	0.01	3	1161	97	2.13	8	2	35	<5	<0.01	<10	10	36	<10	290	3
48851	2.6	1.22	47	115	<0.5	6	0.38	3	14	7	86	4.16	<1	0.27	12	0.62	1004	5	0.01	3	1164	44	1.77	<5	2	24	<5	<0.01	<10	12	32	<10	187	2
48852	6.8	0.39	386	59	<0.5	7	0.26	10	11	18	112	4.03	1	0.20	<10	0.13	310	13	0.01	2	791	577	3.72	16	1	17	<5	<0.01	<10	<10	10	<10	1042	2
48853	5.3	0.26	317	45	<0.5	6	0.41	11	13	<1	109	4.67	<1	0.12	<10	0.18	487	16	<0.01	2	963	276	4.17	12	1	26	<5	<0.01	<10	<10	9	<10	1013	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2278RJ

Date : Jul-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
48854	6.1	0.36	367	84	<0.5	8	1.02	3	12	26	87	4.17	<1	0.26	<10	0.33	784	16	0.01	2	918	87	3.45	13	1	107	<5	<0.01	<10	<10	9	<10	277	2
48855	15.5	0.35	685	77	<0.5	<5	0.46	9	11	19	89	4.11	<1	0.21	<10	0.12	378	30	0.01	2	784	273	3.48	28	1	21	<5	<0.01	<10	<10	10	<10	913	2
48856	>200.0	0.14	1448	26	<0.5	15	0.95	176	5	73	669	7.74	7	0.08	34	0.04	382	8	<0.01	2	158	8429	>5.00	143	<1	17	<5	<0.01	<10	35	7	<10	>10000	4
48857	>200.0	0.15	920	31	<0.5	<5	1.19	102	4	69	435	4.80	13	0.07	34	0.05	496	13	<0.01	2	108	4687	>5.00	98	<1	18	<5	<0.01	<10	34	7	<10	>10000	2
48858	15.6	0.57	215	67	<0.5	8	1.53	10	12	37	60	4.07	<1	0.16	<10	0.29	868	20	0.01	2	812	671	3.13	12	1	56	<5	<0.01	<10	<10	24	<10	1209	2
48859	26.6	1.57	189	108	<0.5	6	2.46	3	16	6	278	4.69	<1	0.27	<10	0.84	1575	16	0.01	2	1402	27	1.18	11	3	95	<5	<0.01	<10	<10	47	<10	292	2
48860	<0.2	0.87	<5	217	<0.5	<5	0.42	1	6	62	3	1.79	<1	0.42	<10	0.53	500	<2	0.06	5	697	8	0.01	5	2	36	6	0.11	<10	<10	34	<10	42	2
48861	>200.0	0.62	2030	82	<0.5	51	3.59	2	54	18	2226	2.66	1	0.06	<10	0.21	717	141	0.04	21	819	362	0.59	521	1	131	<5	0.02	<10	<10	15	21	269	5
48862	4.1	1.31	154	112	<0.5	6	5.65	2	13	6	254	3.93	<1	0.31	<10	0.64	1805	19	0.01	1	1261	23	1.40	<5	2	197	<5	<0.01	<10	<10	38	<10	184	2
48863	3.1	1.73	68	193	<0.5	9	4.08	3	15	5	245	4.70	<1	0.39	<10	0.74	2026	93	0.01	1	1592	26	0.64	5	3	172	<5	<0.01	<10	<10	58	<10	242	2
48864	3.5	1.48	135	126	0.5	6	2.87	3	20	2	331	4.78	<1	0.36	<10	0.58	1554	41	0.01	2	1747	42	1.50	10	4	96	<5	<0.01	<10	<10	40	<10	293	2
48865	5.5	1.76	46	175	0.5	<5	2.56	4	18	2	610	4.60	<1	0.39	<10	0.77	1686	84	0.01	1	1520	29	0.74	<5	3	107	<5	<0.01	<10	<10	53	<10	321	3
48866	4.1	1.78	30	168	0.6	<5	3.05	4	19	1	335	4.66	<1	0.37	<10	0.84	1749	14	0.01	3	1566	21	0.56	<5	3	137	<5	<0.01	<10	<10	50	<10	357	2
48867	2.9	1.51	27	181	<0.5	<5	4.41	3	15	2	241	4.40	<1	0.35	<10	0.78	2119	18	0.01	1	1421	40	0.53	7	3	321	<5	<0.01	<10	<10	41	<10	248	2
48868	1.6	0.61	42	225	<0.5	5	4.90	3	16	3	132	4.46	<1	0.33	<10	0.85	1828	19	0.01	1	1408	35	0.87	7	3	307	<5	<0.01	<10	<10	25	<10	247	2
48869	2.8	0.67	43	115	<0.5	7	3.74	3	15	3	230	4.54	<1	0.35	<10	0.76	1808	31	0.01	<1	1412	31	0.87	5	3	150	<5	<0.01	<10	<10	31	<10	226	2
48870	1.0	0.39	59	129	<0.5	<5	3.23	3	11	20	116	3.80	<1	0.27	<10	0.62	1386	20	0.02	<1	1139	14	1.01	11	3	173	<5	<0.01	<10	<10	20	<10	191	2
48871	2.5	0.77	40	239	<0.5	<5	4.32	3	12	9	214	4.15	<1	0.24	<10	0.92	1874	70	0.02	<1	1112	17	0.79	7	4	194	<5	<0.01	<10	<10	32	<10	159	2
48872	2.0	0.97	26	138	0.5	<5	2.10	3	17	7	164	5.08	<1	0.35	<10	0.99	1715	7	0.01	1	1451	13	0.77	12	4	94	<5	<0.01	<10	<10	39	<10	190	3
48873	3.1	1.00	62	76	<0.5	8	2.96	2	15	8	196	4.30	<1	0.22	<10	0.74	1562	19	0.01	<1	1258	14	1.45	6	3	144	<5	<0.01	<10	<10	36	<10	171	2
48874	2.8	0.77	24	87	<0.5	7	6.08	2	17	7	229	3.98	<1	0.26	<10	0.88	2259	39	0.02	1	1193	16	0.40	<5	4	195	<5	<0.01	<10	<10	42	<10	198	2
48875	3.1	0.43	25	86	<0.5	<5	3.79	3	17	4	255	4.38	<1	0.31	<10	0.99	2148	24	0.02	<1	1255	21	0.56	8	4	185	<5	<0.01	<10	<10	22	<10	192	2
48876	2.3	0.66	26	82	<0.5	5	3.56	3	16	12	186	4.23	<1	0.27	<10	0.76	1812	17	0.02	1	988	30	0.54	<5	4	126	<5	<0.01	<10	<10	35	<10	234	2
48877	2.8	1.05	38	101	<0.5	5	2.19	3	31	5	188	4.52	<1	0.30	<10	0.84	1762	14	0.02	3	1169	29	0.41	8	3	85	<5	<0.01	<10	<10	45	<10	237	2
48878	4.8	0.39	74	84	<0.5	<5	2.89	3	14	6	226	4.75	<1	0.29	<10	0.72	1704	20	0.01	<1	1057	57	1.36	10	3	118	<5	<0.01	<10	<10	17	<10	177	2
48879	2.7	0.46	50	97	<0.5	<5	2.80	2	14	5	151	4.45	<1	0.30	<10	0.84	1606	10	0.01	1	1094	41	1.10	7	3	165	<5	<0.01	<10	<10	21	<10	151	2
48880	2.1	1.15	40	100	<0.5	9	3.58	3	14	3	139	4.65	<1	0.24	<10	0.86	2027	6	0.02	2	1096	23	1.11	7	4	135	<5	<0.01	<10	<10	56	<10	208	2
48881	1.9	0.41	54	124	<0.5	<5	2.80	3	17	4	108	4.92	<1	0.30	<10	0.71	1733	9	0.01	1	1241	25	1.19	<5	3	112	<5	<0.01	<10	<10	22	<10	184	2
48882	2.1	0.47	75	166	<0.5	5	3.46	3	20	3	98	4.54	1	0.34	<10	0.79	1683	11	0.01	<1	1282	36	1.23	12	3	169	<5	<0.01	<10	<10	18	<10	194	2
48883	3.4	0.41	338	104	<0.5	<5	8.73	3	14	14	54	4.41	<1	0.33	<10	0.67	2771	19	0.01	1	994	53	2.45	15	2	309	<5	<0.01	<10	<10	11	<10	216	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2278RJ

Date : Jul-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
48884	3.2	0.48	173	77	<0.5	<5	2.96	3	13	15	150	4.42	1	0.30	<10	0.60	1370	7	0.01	2	1067	84	2.68	<5	2	124	<5	<0.01	<10	<10	16	<10	239	2
48885	2.7	0.60	21	97	<0.5	6	3.15	3	16	7	228	4.49	<1	0.30	<10	0.93	1893	14	0.01	2	1256	53	0.86	6	3	135	<5	<0.01	<10	<10	23	<10	202	2
48886	9.4	0.29	294	51	<0.5	6	3.78	13	12	19	109	4.76	1	0.22	<10	0.42	1436	9	0.01	2	828	721	4.22	12	2	216	<5	<0.01	<10	<10	8	<10	1579	2
48887	3.1	0.42	58	120	<0.5	5	3.11	3	14	6	150	4.61	<1	0.34	<10	0.87	1902	11	0.01	1	1188	21	1.54	10	3	198	<5	<0.01	<10	<10	11	<10	178	2
48888	3.2	0.36	98	65	<0.5	5	2.95	6	17	13	172	4.81	1	0.28	<10	0.66	1382	17	0.01	2	1092	99	3.14	9	2	135	<5	<0.01	<10	<10	11	<10	654	2
48889	3.9	0.30	215	59	<0.5	6	10.14	5	10	20	57	4.10	<1	0.26	<10	0.38	2421	6	0.01	<1	676	128	3.59	11	2	217	<5	<0.01	<10	<10	8	<10	440	2
48890	3.9	0.35	62	69	<0.5	<5	6.51	2	12	13	257	3.51	<1	0.28	<10	0.49	1980	13	0.01	2	998	19	1.52	8	3	175	<5	<0.01	<10	<10	13	<10	137	2
48891	1.8	0.40	97	81	<0.5	<5	4.90	3	14	9	55	4.94	<1	0.29	<10	0.68	1930	7	0.01	1	1153	20	2.44	9	2	156	<5	<0.01	<10	<10	19	<10	127	2
48892	2.4	0.53	55	93	<0.5	6	5.04	2	12	12	90	3.80	<1	0.26	<10	0.73	1699	7	0.01	3	1157	54	1.08	6	3	184	<5	<0.01	<10	<10	23	<10	123	2
48893	1.1	1.37	40	99	<0.5	5	4.60	2	15	7	67	4.41	<1	0.24	<10	0.81	1844	3	0.02	1	1197	11	0.70	6	3	127	<5	<0.01	<10	<10	57	<10	128	2
48894	2.2	1.52	54	191	<0.5	6	6.73	2	13	6	205	4.27	<1	0.22	<10	0.99	2501	4	0.02	1	1137	26	0.44	<5	4	272	<5	<0.01	<10	<10	61	<10	126	2
48895	4.1	1.13	111	88	<0.5	<5	5.13	2	14	11	205	4.08	<1	0.28	<10	0.58	1741	4	0.01	1	1085	46	1.76	8	2	121	<5	<0.01	<10	<10	37	<10	137	2
48896	2.0	1.74	33	101	0.5	5	4.16	2	15	4	234	4.31	<1	0.28	<10	0.87	1739	4	0.01	2	1275	12	0.32	<5	3	137	<5	<0.01	<10	<10	52	<10	141	2
48897	1.4	1.26	39	64	<0.5	<5	2.88	2	8	34	41	3.35	<1	0.18	<10	0.71	1399	10	0.02	3	826	10	0.62	6	3	87	<5	<0.01	<10	<10	40	<10	118	2
48898	1.2	1.19	36	66	<0.5	<5	3.17	2	8	25	49	3.18	<1	0.19	<10	0.68	1366	5	0.02	3	808	11	0.56	<5	3	98	<5	<0.01	<10	<10	36	<10	126	2
48899	5.7	1.07	90	68	<0.5	5	2.41	27	7	38	128	4.08	<1	0.19	<10	0.56	1209	5	0.01	2	745	1221	2.24	9	2	56	<5	<0.01	<10	<10	35	<10	3348	2
48900	1.2	1.02	70	105	<0.5	<5	3.06	2	8	31	48	3.72	<1	0.19	<10	0.60	1301	10	0.01	1	813	16	1.68	7	2	116	<5	<0.01	<10	<10	35	<10	168	2
48901	1.5	1.03	66	65	<0.5	<5	4.31	2	7	41	44	3.33	<1	0.17	<10	0.58	1525	10	0.01	2	686	20	1.09	6	3	138	<5	<0.01	<10	<10	33	<10	175	2
48902	1.3	0.98	51	78	<0.5	<5	2.71	2	7	30	59	3.49	<1	0.15	<10	0.73	1335	10	0.02	2	767	10	0.85	8	3	103	<5	<0.01	<10	<10	38	<10	131	2
48903	16.6	0.45	112	56	<0.5	<5	0.58	65	6	65	150	4.34	<1	0.17	<10	0.38	610	6	0.01	2	565	1723	3.26	13	1	30	<5	<0.01	<10	<10	19	<10	8368	2
48904	11.2	0.20	158	46	<0.5	<5	0.61	29	4	73	64	3.16	<1	0.13	<10	0.15	374	3	0.01	4	330	1191	2.59	8	1	30	<5	<0.01	<10	<10	7	<10	3800	2
48905	16.6	0.60	185	80	0.5	8	2.85	38	14	81	212	5.98	2	0.37	<10	0.66	1685	11	0.01	4	1150	2967	3.32	13	3	156	<5	<0.01	<10	<10	30	<10	4286	3
48906	1.6	1.01	80	155	<0.5	<5	3.10	2	12	24	95	3.79	<1	0.21	<10	0.66	1600	7	0.01	3	895	74	0.49	<5	3	97	<5	<0.01	<10	<10	46	<10	163	2
48907	1.3	1.65	28	77	<0.5	5	4.02	2	16	22	106	4.46	<1	0.21	<10	0.86	2101	5	0.02	4	1018	24	0.32	6	4	168	<5	<0.01	<10	<10	69	<10	159	2
48908	1.8	1.90	16	69	<0.5	<5	3.80	3	20	12	228	5.11	<1	0.18	<10	0.94	2261	11	0.02	4	1118	10	0.21	<5	4	156	<5	<0.01	<10	<10	80	<10	156	3
48909	1.9	1.95	60	78	<0.5	8	3.37	3	19	7	139	5.35	<1	0.23	<10	1.01	2251	9	0.01	3	1242	36	0.78	5	4	132	<5	0.01	<10	<10	83	<10	159	3
48910	2.7	1.26	160	79	<0.5	<5	4.80	2	19	9	107	4.71	<1	0.25	<10	0.59	2250	7	0.01	2	1167	18	2.22	6	3	139	<5	<0.01	<10	<10	56	<10	100	3
48911	2.4	1.69	129	67	<0.5	7	2.85	3	22	7	165	5.22	<1	0.27	<10	0.85	1901	8	0.01	3	1256	15	1.64	9	3	98	<5	0.01	<10	<10	68	<10	120	3
48912	2.8	1.86	93	74	<0.5	11	3.53	3	20	7	173	5.42	<1	0.22	<10	1.00	1970	13	0.01	3	1437	16	1.71	7	5	125	<5	0.01	<10	<10	83	<10	148	3
48913	2.5	2.01	80	73	<0.5	9	3.69	3	20	4	178	5.53	<1	0.20	<10	1.24	2117	12	0.01	3	1466	14	1.48	<5	5	143	<5	0.01	<10	<10	95	<10	147	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth

Sample type:

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2278RJ

Date : Jul-04-08

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
48914	2.9	1.76	60	86	<0.5	7	5.54	3	18	9	179	4.77	<1	0.22	<10	1.06	2244	13	0.01	3	1269	10	1.23	6	5	182	<5	0.01	<10	<10	76	<10	113	3
48915	2.7	2.07	36	79	<0.5	7	4.02	3	21	3	230	5.67	<1	0.18	<10	1.13	1899	9	0.02	3	1434	9	0.91	7	7	160	<5	0.06	<10	<10	114	<10	170	3
48916	2.5	1.21	180	68	<0.5	8	4.00	3	14	15	74	4.43	<1	0.21	<10	0.75	2658	10	0.01	1	1043	20	2.24	11	3	142	<5	0.01	<10	<10	47	<10	126	3
48917	3.1	0.99	121	89	<0.5	7	3.25	3	18	7	139	4.98	<1	0.25	<10	0.80	2628	8	0.01	3	1280	63	2.49	8	3	120	<5	<0.01	<10	<10	49	<10	167	3
48918	3.0	1.17	65	68	<0.5	5	3.13	2	14	19	137	4.21	<1	0.19	<10	0.72	2286	6	0.01	1	1089	18	1.35	9	3	76	<5	<0.01	<10	<10	49	<10	111	2
48919	4.9	1.44	54	110	<0.5	8	3.16	2	14	13	189	4.47	<1	0.18	<10	0.84	2640	7	0.01	2	1116	17	1.20	11	4	120	<5	<0.01	<10	<10	64	<10	147	2
48920	6.3	0.79	84	86	<0.5	5	3.73	3	13	23	265	4.42	<1	0.21	<10	0.77	3107	6	0.01	2	1127	27	2.10	11	3	145	<5	<0.01	<10	<10	35	<10	176	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2297-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment 3**
Attn: **Sue Deane**

Jul-09-08

We hereby certify the following assay of 24 core samples submitted Jun-23-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
48921	0.35	0.33	3.0
48922	0.21		2.2
48923	0.26		2.5
48924	0.13		2.8
48925	0.05		0.6
48926	0.03		0.9
48927	0.06		2.4
48928	0.10		2.8
48929	0.57		1.3
48930	0.16	0.16	1.0
48931	5.36		1.3
48932	0.15		1.7
48933	0.25		4.9
48934	0.16		2.9
48935	0.01		<0.2
48936	1.75		165.0
48937	0.08		1.7
48938	0.07		1.0
48939	0.07		0.2
48940	0.07	0.08	<0.2
48941	0.06		3.7
48942	0.05		2.8
48943	0.05		2.0
48944	0.06		2.1
*0218	0.89		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2297-RA2

Company: **Ascot Resources Ltd**
 Project: **Dilworth/PO#shipment 3**
 Attn: **Sue Deane**

Jul-09-08

We hereby certify the following assay of 24 core samples submitted Jun-23-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %	Zn %
48945	0.07	0.03	1.5		
48946	0.11		2.1		
48947	0.04		0.2		
48948	0.15		1.6		
48949	0.21		5.1		
48950	0.13		2.0		
48951	0.09		14.6		1.21
48952	0.14		3.9		
48953	0.10		3.7		
48954	0.09	0.08	3.9		
48955	0.04		1.7		
48956	0.26		15.4	1.27	1.39
48957	0.07		0.8		
48958	0.12		1.3		
48959	0.10		1.7		
48960	0.35		13.0		2.08
48961	0.10		1.9		
48962	0.09		1.0		
48963	0.30		12.8		1.41
48964	0.98	0.95	10.3		
48965	0.19		2.7		
48966	0.15		2.9		
48967	0.26		2.4		
48968	0.37		2.0		
*0218	0.90				
*CCu-1c				0.33	3.97
*BLANK	<0.01			<0.01	<0.01

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2297-RA3

Company: **Ascot Resources Ltd**
 Project: **Dilworth/PO#shipment 3**
 Attn: **Sue Deane**

Jul-09-08

We hereby certify the following assay of 24 core samples submitted Jun-23-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
48969	0.09	0.10	2.2	
48970	0.03		1.6	
48971	0.21		1.4	
48972	0.13		2.4	
48973	0.19		2.3	
48974	0.40		2.4	
48975	0.27		4.0	
48976	0.15		2.4	
48977	0.26		1.2	
48978	0.36	0.37	1.0	
48979	0.11		1.5	
48980	0.17		0.5	
48981	0.44		1.6	
48982	0.20		14.4	1.16
48983	0.20		3.3	1.45
48984	0.36		3.1	1.84
48985	0.08		4.4	
48986	0.17		7.7	1.19
48987	0.07		6.1	
48988	0.11	0.14	4.5	
48989	<0.01		0.2	
48990	0.42		0.4	
48991	0.08		3.2	
48992	0.25		3.2	
*0218	0.85			
*CCu-1c				3.97
*BLANK	<0.01			<0.01

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2297-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment 3**
Attn: **Sue Deane**

Jul-09-08

We hereby certify the following assay of 24 core samples submitted Jun-23-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
48993	0.57	0.61	4.2
48994	0.42		6.0
48995	0.38		5.0
48996	0.14		5.7
48997	0.07		3.2
48998	0.10		5.4
48999	0.05		5.7
49000	0.08		1.4
83501	0.07		2.8
83502	0.03	0.04	2.1
83503	0.06		4.8
83504	0.03		0.8
83505	0.07		2.1
83506	0.01		0.7
83507	0.22		5.0
83508	1.90		6.8
83509	8.12		9.9
83510	1.48		7.0
83511	0.14		11.5
83512	0.20	0.16	5.2
83513	0.13		2.7
83514	0.11		2.6
83515	0.15		2.3
83516	0.29		5.8
*0218	0.87		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2297-RA5

Company: **Ascot Resources Ltd**
 Project: **Dilworth/PO#shipment 3**
 Attn: **Sue Deane**

Jul-09-08

We hereby certify the following assay of 15 core samples submitted Jun-23-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne	Zn %
83517	1.82	2.26	3.3		
83518	0.21		7.9		
83519	0.33		4.9		
83520	0.18		28.0		
83521	2.05		>200	1294	
83522	0.39		45.6		
83523	0.51		111.6		
83524	2.14		>200	792.9	1.56
83525	0.17		11.3		
83526	0.18	0.14	6.5		
83527	0.01		1.4		
83528	1.33		>200	227.0	
83529	0.25		5.7		
83530	0.14		2.0		
SD08-01	1.58		>200	464.9	
*0218	0.91				
*CCu-1c				131.4	3.97
*BLANK	<0.01			<0.1	<0.01

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2297RJ**

Date : Jul-09-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment 3

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
48921	3.0	0.33	150	73	<0.5	<5	5.35	2	13	20	120	4.62	<1	0.26	<10	0.67	2855	8	0.01	2	954	42	2.38	5	2	250	5	<0.01	<10	<10	20	<10	117	3
48922	2.2	0.96	144	74	<0.5	<5	3.35	2	16	28	84	5.16	<1	0.25	<10	0.81	4036	3	0.01	3	992	44	2.88	<5	2	107	<5	<0.01	<10	<10	43	<10	133	3
48923	2.5	0.73	143	75	<0.5	<5	3.85	3	13	33	34	4.10	<1	0.22	<10	0.65	4235	3	0.01	3	896	306	2.77	<5	2	129	<5	<0.01	<10	<10	31	<10	407	2
48924	2.8	0.55	74	53	<0.5	<5	4.69	5	9	48	105	3.09	<1	0.22	<10	0.43	4070	5	0.01	2	748	245	2.05	<5	1	162	<5	<0.01	<10	<10	17	<10	688	2
48925	0.6	0.74	71	64	<0.5	<5	2.98	2	7	44	14	2.86	<1	0.21	<10	0.58	3407	7	0.01	2	705	46	1.37	<5	2	87	5	<0.01	<10	<10	18	<10	227	2
48926	0.9	0.77	57	65	<0.5	<5	2.67	1	7	58	17	2.99	<1	0.19	<10	0.56	3066	<2	0.01	3	644	79	1.49	<5	2	70	5	<0.01	<10	<10	21	<10	140	2
48927	2.4	0.47	142	68	<0.5	<5	2.01	2	10	53	25	4.07	<1	0.24	<10	0.37	2116	4	0.01	3	736	173	3.37	<5	1	73	<5	<0.01	<10	<10	16	<10	256	3
48928	2.8	0.26	135	60	<0.5	<5	2.17	2	9	52	38	3.59	<1	0.22	<10	0.22	1764	<2	0.01	4	708	138	3.26	<5	1	69	<5	<0.01	<10	<10	8	<10	267	2
48929	1.3	0.26	103	47	<0.5	<5	2.70	1	5	63	<1	1.98	<1	0.18	<10	0.12	1688	3	<0.01	2	377	100	1.66	<5	1	75	<5	<0.01	<10	<10	6	<10	115	2
48930	1.0	0.16	102	54	<0.5	<5	6.09	1	4	87	28	1.93	<1	0.14	<10	0.24	2208	2	<0.01	3	271	118	1.33	<5	1	315	<5	<0.01	<10	<10	4	<10	162	1
48931	1.3	0.44	100	67	<0.5	<5	3.24	2	8	60	39	3.33	<1	0.20	<10	0.43	2720	2	0.01	3	597	35	2.03	<5	1	160	<5	<0.01	<10	<10	15	<10	207	2
48932	1.7	1.06	288	70	<0.5	<5	2.47	2	10	48	126	3.72	<1	0.18	<10	0.63	2632	8	0.01	3	707	69	1.50	<5	2	81	<5	<0.01	<10	<10	39	<10	237	2
48933	4.9	0.61	501	69	<0.5	<5	5.08	3	8	47	36	3.01	<1	0.16	<10	0.34	3416	4	0.01	3	594	478	1.98	6	1	159	<5	<0.01	<10	<10	21	<10	523	2
48934	2.9	0.76	444	64	<0.5	<5	4.29	4	8	62	43	3.15	<1	0.19	<10	0.43	3761	2	0.01	4	557	683	1.88	<5	1	135	<5	<0.01	<10	<10	21	<10	806	2
48935	<0.2	0.94	<5	237	0.6	<5	0.44	<1	7	98	<1	2.00	<1	0.52	<10	0.62	571	<2	0.06	5	770	3	0.01	<5	2	51	<5	0.12	<10	<10	39	<10	53	2
48936	165.0	0.66	200	149	<0.5	95	4.35	2	17	20	4017	3.03	4	0.16	<10	0.19	519	77	0.03	34	791	215	1.29	262	1	177	7	0.05	<10	<10	21	25	239	8
48937	1.7	1.18	37	57	<0.5	<5	3.57	2	9	45	57	3.34	<1	0.22	<10	0.66	4044	3	0.01	2	721	171	1.01	<5	2	118	<5	<0.01	<10	<10	35	<10	302	2
48938	1.0	1.61	34	63	<0.5	<5	2.77	2	12	49	38	4.40	<1	0.18	<10	1.00	3070	5	0.01	3	730	20	1.00	<5	3	90	<5	0.02	<10	<10	60	<10	205	3
48939	0.2	1.47	16	55	<0.5	<5	3.79	1	10	34	18	3.84	<1	0.16	<10	0.85	3070	2	0.01	3	700	17	0.54	<5	3	167	<5	0.01	<10	<10	47	<10	147	2
48940	<0.2	1.49	19	80	<0.5	<5	2.59	2	10	43	31	4.06	<1	0.16	<10	0.87	2634	3	0.01	3	810	5	0.49	<5	3	153	<5	<0.01	<10	<10	46	<10	196	2
48941	3.7	1.43	45	58	<0.5	<5	4.98	2	12	24	59	4.18	1	0.20	<10	0.81	4441	2	0.01	3	829	116	1.20	<5	3	143	<5	<0.01	<10	<10	55	<10	209	2
48942	2.8	1.33	35	54	<0.5	<5	6.27	3	10	35	116	3.61	<1	0.19	<10	0.71	7458	<2	0.01	3	782	250	1.00	<5	3	168	<5	0.01	<10	<10	41	<10	469	2
48943	2.0	1.52	39	55	<0.5	<5	2.95	2	12	33	88	4.17	<1	0.21	<10	0.90	5058	3	0.01	3	884	68	1.16	<5	3	77	<5	0.02	<10	<10	57	<10	238	3
48944	2.1	1.40	34	50	<0.5	<5	3.68	2	11	43	79	4.03	<1	0.20	<10	0.79	3957	2	0.01	3	831	108	1.17	<5	3	101	<5	0.02	<10	<10	50	<10	339	3
48945	1.5	1.87	58	64	<0.5	<5	4.56	2	15	45	68	5.71	<1	0.23	<10	1.00	3974	5	0.01	4	1010	54	1.48	<5	4	109	6	0.01	<10	<10	78	<10	149	4
48946	2.1	1.08	95	107	<0.5	<5	6.41	2	15	39	116	4.38	<1	0.27	<10	0.62	2915	5	0.01	4	976	91	1.96	5	3	163	6	<0.01	<10	<10	46	<10	165	3
48947	0.2	1.07	43	96	<0.5	<5	3.34	1	12	66	19	3.28	<1	0.21	<10	0.68	1728	4	0.01	3	717	33	1.10	<5	2	91	7	<0.01	<10	<10	31	<10	62	2
48948	1.6	1.60	32	99	<0.5	<5	5.19	2	18	112	186	4.54	<1	0.17	<10	0.86	2003	15	0.01	15	985	18	0.73	<5	8	109	7	<0.01	<10	<10	98	<10	138	3
48949	5.1	2.03	110	54	<0.5	<5	9.42	51	26	191	229	6.34	<1	0.09	<10	1.37	3812	24	0.01	29	1061	1772	2.36	6	17	190	9	0.01	<10	<10	154	<10	5633	4
48950	2.0	2.17	177	58	0.5	<5	10.14	8	25	219	111	6.31	<1	0.09	<10	1.55	3593	17	0.01	31	1271	794	1.64	6	22	209	8	0.02	<10	<10	170	<10	846	5

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2297RJ**

Date : Jul-09-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment 3

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
48951	14.6	2.11	92	45	<0.5	<5	6.89	109	24	214	751	6.89	1	0.07	<10	1.71	3254	32	0.01	31	1302	6683	3.57	16	15	130	6	0.01	<10	<10	140	<10	>10000	5
48952	3.9	2.15	121	54	<0.5	<5	9.72	20	33	260	329	6.79	<1	0.09	<10	1.46	3514	16	0.01	40	1553	2100	2.39	8	22	168	7	0.02	<10	<10	187	<10	2149	5
48953	3.7	2.08	92	70	<0.5	<5	8.37	31	26	207	334	5.61	<1	0.09	<10	1.62	3218	22	0.01	29	1347	1819	1.59	7	17	168	7	0.01	<10	<10	153	<10	3404	4
48954	3.9	2.29	94	36	<0.5	<5	5.82	41	23	193	207	6.25	<1	0.06	<10	1.84	3166	17	0.01	29	1172	3062	2.10	7	17	141	5	0.02	<10	<10	146	<10	4374	5
48955	1.7	2.10	79	55	0.5	<5	11.28	12	27	231	196	5.25	1	0.12	<10	1.48	4317	21	0.01	33	1479	775	0.91	7	20	223	8	0.03	<10	<10	165	<10	1368	4
48956	15.4	1.82	192	41	<0.5	<5	4.90	120	24	112	212	8.38	1	0.10	<10	1.46	2597	21	0.01	20	878	>10000	>5.00	14	11	101	5	0.01	<10	<10	114	<10	>10000	5
48957	0.8	2.26	39	81	0.5	<5	9.23	9	25	194	118	5.67	<1	0.22	<10	1.57	2666	16	0.02	26	1200	201	0.91	5	20	197	7	0.04	<10	<10	157	<10	975	4
48958	1.3	1.04	48	64	<0.5	<5	8.71	6	17	107	98	3.31	<1	0.13	<10	0.64	2277	15	0.01	14	730	685	1.12	<5	7	166	7	0.01	<10	<10	63	<10	667	2
48959	1.7	1.34	104	72	<0.5	<5	4.43	7	11	37	85	4.53	<1	0.19	<10	0.99	2265	20	0.01	5	829	830	2.01	<5	4	110	7	<0.01	<10	<10	52	<10	696	3
48960	13.0	1.61	546	30	<0.5	<5	3.11	204	20	33	329	11.19	<1	0.08	<10	1.34	2701	7	0.01	6	571	9051	>5.00	18	3	84	<5	<0.01	<10	<10	61	<10	>10000	7
48961	1.9	2.09	91	59	<0.5	<5	4.47	65	18	66	95	6.74	<1	0.13	<10	1.49	2931	11	0.01	10	911	1195	2.95	6	6	124	6	<0.01	<10	<10	86	<10	7678	4
48962	1.0	1.64	116	65	<0.5	<5	4.79	36	10	35	54	5.01	<1	0.15	<10	1.20	2629	22	0.01	3	738	752	2.06	5	4	84	7	<0.01	<10	<10	57	<10	4062	3
48963	12.8	1.60	558	33	<0.5	<5	3.03	204	20	34	329	11.45	1	0.08	<10	1.32	2667	7	<0.01	6	594	9074	>5.00	19	3	79	<5	<0.01	<10	<10	63	<10	>10000	7
48964	10.3	0.81	750	18	<0.5	<5	5.46	50	10	26	494	7.87	<1	0.03	<10	0.66	3036	<2	<0.01	5	265	6516	4.69	14	2	119	5	<0.01	<10	<10	33	<10	5616	5
48965	2.7	1.23	216	45	<0.5	<5	5.17	48	10	39	93	5.12	<1	0.13	<10	0.83	2342	33	0.01	3	515	586	3.16	5	3	97	6	<0.01	<10	<10	40	<10	5463	3
48966	2.9	0.88	152	33	<0.5	<5	>15.00	24	9	18	107	3.73	<1	0.07	<10	0.56	5457	6	0.01	4	346	906	1.83	6	3	345	7	0.01	<10	<10	41	<10	2663	2
48967	2.4	2.37	135	68	<0.5	<5	2.84	22	28	53	236	7.75	<1	0.17	<10	1.52	2345	17	0.01	14	1331	272	3.00	<5	9	78	<5	0.01	<10	<10	147	<10	2262	5
48968	2.0	2.82	56	61	<0.5	<5	3.35	14	24	50	240	7.34	<1	0.15	<10	1.95	2747	28	0.01	14	1483	456	1.37	<5	11	118	<5	0.01	<10	<10	160	<10	1455	4
48969	2.2	2.77	47	46	<0.5	<5	4.66	29	14	65	150	6.33	<1	0.08	<10	2.29	3178	10	<0.01	11	1108	433	1.05	5	11	11	<5	0.01	<10	<10	148	<10	3079	4
48970	1.6	2.47	31	55	<0.5	<5	3.50	6	16	62	222	5.91	<1	0.12	<10	1.80	2365	44	<0.01	11	1244	134	0.64	5	11	33	<5	0.01	<10	<10	141	<10	601	3
48971	1.4	1.53	74	46	<0.5	<5	6.41	3	10	27	53	4.65	<1	0.14	<10	0.94	2414	8	<0.01	5	709	54	1.41	<5	6	57	<5	<0.01	<10	<10	54	<10	192	3
48972	2.4	1.48	143	76	<0.5	5	2.39	9	10	36	63	4.82	<1	0.15	<10	0.94	1538	14	<0.01	2	726	212	1.90	5	3	45	<5	0.01	<10	<10	48	<10	805	3
48973	2.3	1.48	65	63	<0.5	5	2.74	5	15	53	153	4.60	<1	0.19	<10	0.78	1320	39	0.01	8	1016	30	1.38	<5	4	61	<5	0.01	<10	<10	58	<10	370	3
48974	2.4	2.07	49	58	<0.5	<5	3.87	3	21	48	314	5.31	<1	0.18	<10	1.37	1773	32	<0.01	13	1209	16	0.72	<5	10	<1	<5	0.01	<10	<10	126	<10	211	3
48975	4.0	2.55	24	68	<0.5	11	4.66	3	31	46	410	6.37	<1	0.24	<10	1.62	2102	38	0.01	15	1727	29	0.69	<5	9	138	<5	0.01	<10	<10	130	<10	154	3
48976	2.4	2.58	34	56	<0.5	6	6.08	5	24	51	302	6.33	1	0.15	<10	1.73	2383	51	0.01	13	1497	16	0.59	<5	15	134	<5	0.07	<10	<10	184	<10	275	4
48977	1.2	2.43	12	47	<0.5	9	6.14	3	21	47	198	5.49	<1	0.09	<10	2.00	2016	25	0.01	11	1346	10	0.38	<5	16	121	<5	0.12	<10	<10	182	<10	204	3
48978	1.0	2.48	10	53	<0.5	7	5.09	3	23	47	315	5.42	<1	0.10	<10	2.14	1713	42	0.01	12	1389	9	0.26	<5	14	103	<5	0.13	<10	<10	180	<10	186	3
48979	1.5	2.28	48	51	<0.5	6	8.12	4	23	174	119	5.50	1	0.09	<10	1.48	2593	9	0.01	27	1404	16	0.25	<5	17	173	<5	0.04	<10	<10	171	<10	230	4
48980	0.5	2.15	27	69	0.5	5	8.96	4	21	204	80	4.94	<1	0.05	<10	1.73	2415	29	0.01	26	1375	31	0.13	5	18	199	<5	0.06	<10	<10	166	<10	248	5

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2297RJ**

Date : Jul-09-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment 3

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
48981	1.6	1.64	20	51	<0.5	<5	5.56	3	18	111	161	3.69	<1	0.07	<10	1.47	1622	49	0.01	17	1171	10	0.20	9	11	118	<5	0.09	<10	<10	115	<10	140	5
48982	14.4	1.23	125	25	<0.5	12	8.66	107	12	28	643	4.33	<1	0.05	<10	0.91	2857	20	0.01	2	474	1695	2.50	9	5	95	<5	0.03	<10	<10	50	<10	>10000	3
48983	3.3	1.34	33	35	<0.5	7	5.86	132	14	26	177	4.15	1	0.08	<10	0.96	2100	14	0.01	3	591	130	2.12	11	5	56	<5	0.05	<10	<10	55	<10	>10000	3
48984	3.1	1.52	62	27	<0.5	8	5.70	168	15	29	111	5.85	<1	0.05	<10	1.09	2441	14	0.01	2	534	155	3.93	9	5	60	<5	0.04	<10	<10	61	<10	>10000	3
48985	4.4	1.18	44	24	<0.5	7	10.21	69	11	62	120	4.02	<1	0.04	<10	0.85	3278	40	0.01	7	478	415	1.89	6	7	123	<5	0.03	<10	<10	60	<10	7151	2
48986	7.7	1.20	65	25	<0.5	12	8.10	110	18	122	253	4.05	<1	0.05	<10	0.81	2895	173	<0.01	14	773	1147	2.09	8	8	105	<5	0.03	<10	<10	73	<10	>10000	3
48987	6.1	0.87	154	24	<0.5	<5	6.34	69	12	107	260	3.00	<1	0.05	<10	0.51	2085	26	<0.01	12	734	724	1.24	13	7	83	<5	0.03	<10	<10	63	<10	7633	2
48988	4.5	1.88	40	22	<0.5	10	9.12	57	16	158	196	5.29	<1	0.03	<10	1.41	3093	25	<0.01	17	892	349	1.58	8	11	153	<5	0.04	<10	<10	114	<10	6197	4
48989	0.2	0.83	<5	198	<0.5	<5	0.74	3	6	69	11	1.87	<1	0.39	<10	0.54	579	<2	0.04	4	712	32	0.04	<5	2	32	7	0.12	<10	<10	35	<10	339	2
48990	0.4	0.90	6929	18	<0.5	19	5.47	2	166	10	71	3.53	<1	0.04	<10	0.22	625	13	0.06	29	1229	14	1.16	6	1	77	<5	0.04	<10	<10	31	<10	98	9
48991	3.2	1.82	724	39	<0.5	8	8.68	10	22	183	221	4.86	<1	0.08	<10	1.31	3124	40	0.01	25	1243	72	1.02	16	12	135	<5	0.04	<10	<10	124	<10	914	3
48992	3.2	1.80	50	41	<0.5	<5	11.51	7	25	242	345	5.12	<1	0.08	<10	1.04	3365	29	0.01	30	1508	26	0.70	5	20	201	<5	0.07	<10	<10	175	<10	542	4
48993	4.2	1.90	39	40	0.5	<5	6.49	4	25	181	551	5.09	<1	0.09	<10	1.22	2380	70	<0.01	47	1354	16	0.56	9	15	<1	<5	0.08	<10	<10	144	<10	239	5
48994	6.0	2.49	29	80	<0.5	<5	6.28	8	25	204	453	6.52	<1	0.07	<10	1.96	2422	67	<0.01	33	1091	311	0.59	11	16	<1	<5	0.08	<10	<10	162	<10	685	5
48995	5.0	2.06	47	41	<0.5	<5	8.62	4	26	234	441	5.26	<1	0.07	<10	1.50	3015	45	<0.01	33	1356	16	0.60	12	22	<1	<5	0.08	<10	<10	182	<10	248	4
48996	5.7	2.28	117	37	<0.5	<5	6.88	12	25	215	422	5.86	<1	0.08	<10	1.79	3224	39	<0.01	29	1242	190	1.48	13	17	<1	<5	0.04	<10	<10	158	<10	1091	4
48997	3.2	1.91	68	53	<0.5	<5	7.14	4	27	199	301	5.27	<1	0.13	<10	1.18	3305	21	<0.01	33	1309	81	1.04	12	16	<1	<5	0.07	<10	<10	139	<10	296	3
48998	5.4	1.78	97	39	<0.5	<5	8.85	42	18	85	276	4.76	<1	0.07	<10	1.25	3294	29	<0.01	13	875	106	1.21	8	12	<1	<5	0.06	<10	<10	118	<10	3864	3
48999	5.7	2.45	34	61	<0.5	<5	4.53	56	20	86	368	5.34	<1	0.09	<10	1.98	2994	17	<0.01	15	1182	113	0.75	6	14	<1	<5	0.10	<10	<10	173	<10	5343	3
49000	1.4	2.45	54	46	<0.5	<5	5.37	11	19	111	105	5.52	<1	0.09	<10	2.02	3057	30	<0.01	17	1032	90	1.04	8	14	<1	<5	0.08	<10	<10	149	<10	1032	3
83501	2.8	2.81	88	73	<0.5	<5	4.63	16	25	69	293	6.41	<1	0.12	<10	2.21	2684	3	0.02	14	1273	1072	1.48	8	13	<1	<5	0.11	<10	<10	176	<10	1612	4
83502	2.1	2.25	58	85	<0.5	<5	3.52	19	27	64	234	5.38	<1	0.12	<10	1.64	1890	3	0.04	15	1465	615	1.37	6	11	<1	<5	0.13	<10	<10	161	<10	1935	4
83503	4.8	1.86	139	73	<0.5	<5	2.11	84	27	23	431	6.78	<1	0.10	<10	1.41	1535	<2	<0.01	10	1356	2769	4.03	7	7	<1	<5	0.14	<10	<10	122	<10	8452	5
83504	0.8	1.11	39	65	<0.5	<5	1.89	4	20	26	69	3.47	<1	0.10	<10	0.73	1047	3	<0.01	9	1262	87	1.05	6	4	<1	<5	0.15	<10	<10	70	<10	381	4
83505	2.1	1.74	130	48	<0.5	<5	4.53	9	28	39	142	5.70	<1	0.07	<10	1.21	1917	6	<0.01	10	1052	213	1.72	7	9	<1	<5	0.12	<10	<10	116	<10	699	5
83506	0.7	1.16	181	34	<0.5	<5	1.92	2	10	45	37	2.32	<1	0.13	<10	0.85	563	<2	0.01	5	665	118	0.16	5	3	<1	<5	0.09	10	<10	37	<10	157	7
83507	5.0	0.48	504	101	<0.5	<5	1.20	3	10	23	34	3.38	<1	0.25	<10	0.15	449	4	<0.01	3	860	109	2.72	12	1	<1	5	<0.01	<10	<10	13	<10	292	2
83508	6.8	0.25	234	86	<0.5	<5	0.56	6	8	60	26	2.92	<1	0.20	<10	0.03	180	4	<0.01	3	654	195	2.94	10	1	<1	9	<0.01	10	<10	5	<10	667	2
83509	9.9	0.30	372	51	<0.5	5	0.22	9	12	28	64	4.52	<1	0.25	<10	0.05	97	5	<0.01	4	1021	358	4.78	14	1	<1	12	<0.01	<10	<10	7	<10	1041	3
83510	7.0	0.32	328	52	<0.5	6	0.26	6	13	46	145	4.43	<1	0.27	<10	0.07	160	21	<0.01	3	1050	180	4.63	13	1	<1	11	<0.01	<10	<10	8	<10	729	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2297RJ

Date : Jul-09-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment 3

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
83511	11.5	1.19	64	139	<0.5	<5	0.31	3	12	15	44	3.95	<1	0.34	<10	0.61	924	7	<0.01	3	1142	54	1.90	8	2	<1	13	<0.01	<10	<10	29	<10	370	2
83512	5.2	0.89	112	85	<0.5	<5	0.30	31	13	34	166	4.52	1	0.30	<10	0.42	624	13	<0.01	4	1082	722	3.54	11	1	<1	10	<0.01	<10	<10	22	<10	3441	3
83513	2.7	1.39	64	139	<0.5	<5	0.34	2	13	16	97	3.94	<1	0.35	<10	0.73	1016	4	<0.01	3	1144	33	1.56	7	2	<1	10	<0.01	<10	<10	32	<10	116	2
83514	2.6	1.63	52	165	<0.5	<5	0.45	2	13	21	46	4.20	<1	0.33	10	0.97	1267	3	<0.01	4	1177	22	1.25	7	2	<1	10	<0.01	<10	<10	40	<10	101	3
83515	2.3	1.32	93	136	<0.5	<5	0.89	2	13	17	58	4.30	<1	0.34	<10	0.73	1243	6	<0.01	3	1043	39	2.12	7	2	<1	9	<0.01	<10	<10	36	<10	136	3
83516	5.8	1.18	325	152	<0.5	<5	0.49	7	12	28	82	3.79	<1	0.34	<10	0.63	1126	4	<0.01	4	1057	146	1.55	14	2	<1	10	<0.01	<10	<10	33	<10	823	2
83517	3.3	1.28	86	133	<0.5	<5	0.40	2	11	20	93	3.74	<1	0.27	<10	0.67	1155	19	0.01	3	1100	47	0.99	<5	2	21	<5	<0.01	<10	<10	33	<10	132	2
83518	7.9	0.65	502	75	<0.5	<5	0.63	7	15	65	185	6.23	<1	0.29	15	0.50	1046	10	0.01	6	1240	196	4.59	11	2	47	<5	<0.01	<10	15	21	<10	629	3
83519	4.9	0.96	84	106	<0.5	<5	0.41	3	11	21	74	4.05	1	0.31	<10	0.53	1029	<2	<0.01	2	1195	86	2.09	<5	2	19	<5	<0.01	<10	<10	28	<10	288	2
83520	28.0	0.32	250	74	<0.5	<5	0.26	3	10	58	68	3.73	<1	0.24	<10	0.18	647	4	<0.01	3	968	111	2.60	13	1	15	<5	<0.01	<10	<10	9	<10	280	2
83521	>200.0	0.16	1714	16	<0.5	<5	0.09	53	5	104	399	8.16	2	0.09	15	0.03	194	8	<0.01	5	185	4063	>5.00	199	<1	7	<5	<0.01	<10	15	5	<10	8812	4
83522	45.6	0.15	830	50	<0.5	<5	0.44	6	5	141	88	4.05	1	0.11	<10	0.07	386	10	<0.01	4	297	344	3.84	35	<1	19	<5	<0.01	<10	<10	5	<10	742	2
83523	111.6	0.17	716	58	<0.5	<5	0.75	11	5	114	125	3.99	<1	0.10	<10	0.15	624	15	<0.01	4	358	642	3.67	54	1	34	<5	<0.01	<10	<10	8	<10	1519	2
83524	>200.0	0.29	955	25	<0.5	8	1.45	105	11	111	613	7.92	2	0.13	<10	0.14	885	12	<0.01	3	368	5015	>5.00	127	1	62	<5	<0.01	<10	<10	17	<10	>10000	4
83525	11.3	1.26	201	109	<0.5	5	10.99	4	15	14	127	3.95	<1	0.27	<10	0.69	3555	55	0.01	1	961	68	1.52	11	4	385	<5	0.01	<10	<10	49	<10	326	2
83526	6.5	1.63	69	153	0.5	<5	6.08	4	16	23	130	4.12	<1	0.26	<10	0.86	1934	24	0.01	3	1176	32	0.58	9	5	275	<5	0.02	<10	<10	70	<10	302	4
83527	1.4	0.82	<5	203	<0.5	<5	0.42	1	5	96	2	1.79	<1	0.40	<10	0.50	492	<2	0.05	6	738	2	<0.01	<5	2	39	<5	0.12	<10	<10	33	<10	42	2
83528	>200.0	0.67	2086	83	<0.5	50	3.70	2	55	18	2193	2.69	1	0.07	<10	0.21	741	139	0.03	21	828	370	0.61	537	1	128	<5	0.02	<10	<10	16	17	269	6
83529	5.7	1.50	104	142	<0.5	<5	8.85	4	15	12	157	4.17	<1	0.20	<10	0.70	3032	47	0.01	1	916	27	0.56	5	5	346	<5	0.01	<10	<10	75	<10	296	3
83530	2.0	1.79	204	144	0.5	<5	8.31	3	18	9	95	4.63	<1	0.24	<10	1.11	2797	33	<0.01	5	1039	19	0.56	8	7	<1	<5	0.04	<10	<10	103	<10	282	6
SD08-01	>200.0	0.22	338	56	<0.5	<5	0.17	23	8	81	82	3.87	2	0.13	<10	0.02	71	5	0.01	2	575	3591	3.98	95	<1	10	<5	<0.01	<10	<10	5	<10	2780	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Metallic Assay Certificate

8V-2297-RM3

Company: **Ascot Resources Ltd**
Project: Dilworth/PO#shipment 3
Attn: Sue Deane

Jul-09-08

We *hereby certify* the following analysis of 1 pulp sample submitted Jul-14-08

Sample Name	WtTotal g	Wt+150 g	+150Au mg	-150Au g/tonne	Metallic Au g/tonne	Net Au g/tonne
83517 original	116.1	39.1	0.099	1.21	0.86	1.66

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2349-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment 4**
Attn: **Sue Deane**

Jul-12-08

We hereby certify the following assay of 24 core samples submitted Jun-26-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag-Rerun g/tonne	Ag g/tonne
83651	0.14	0.14	2.8	3.0	
83652	0.09		2.7	3.0	
83653	0.13		3.0	2.7	
83654	0.08		1.9	1.9	
83655	0.11		4.1	3.7	
83656	0.21		30.3	33.9	
83657	0.48		59.4	64.9	
83658	0.53		165.0	>200	217.3
83659	0.35		14.6	15.4	
83660	0.26	0.28	5.0	5.1	
83661	<0.01		0.1	0.2	
83662	1.26		143	>200	220.7
83663	0.22		4.3	4.1	
83664	0.26		4.2	4.0	
83665	0.40		7.2	5.8	
83666	0.27		3.9	3.4	
83667	0.14		2.0	2.5	
83668	0.24		2.7	2.5	
83669	0.23		3.0	3.3	
83670	0.21	0.21	0.7	1.0	
83671	0.30		2.3	2.3	
83672	0.15		3.9	3.6	
83673	0.38		14.5	16.7	
83674	0.10		4.0	4.3	
*0218	0.92				
*CCu-1c					130.3
*BLANK	<0.01				<0.1

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2349RJ**

Date : Jul-12-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment 4

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
83651	2.7	0.83	184	71	<0.5	<5	1.07	2	12	47	47	4.93	<1	0.32	<10	0.36	814	4	0.01	5	853	32	4.14	5	1	73	<5	<0.01	<10	<10	27	<10	85	3
83652	2.6	1.34	125	139	<0.5	<5	0.65	3	12	32	69	4.00	<1	0.40	<10	0.60	919	11	0.01	4	1002	75	2.04	<5	2	29	<5	<0.01	<10	<10	38	<10	242	3
83653	2.8	1.10	139	102	<0.5	<5	0.40	2	13	40	101	4.00	<1	0.38	<10	0.42	647	7	0.01	4	1016	42	2.62	<5	2	28	<5	<0.01	<10	<10	26	<10	129	3
83654	1.6	1.37	117	122	<0.5	<5	0.58	2	12	66	57	4.33	<1	0.42	10	0.60	900	4	0.01	5	956	29	2.40	<5	2	40	<5	<0.01	<10	<10	34	<10	126	3
83655	3.9	0.85	140	84	<0.5	<5	0.61	6	10	66	127	3.76	<1	0.32	<10	0.36	671	5	0.01	4	807	98	2.71	6	1	49	<5	<0.01	<10	<10	24	<10	636	2
83656	34.0	0.82	331	73	<0.5	<5	0.69	3	9	105	72	4.14	<1	0.30	10	0.36	806	7	0.01	4	711	205	2.99	8	1	48	<5	<0.01	<10	<10	27	<10	353	3
83657	63.2	0.29	501	69	<0.5	<5	0.90	10	6	97	71	3.52	<1	0.15	<10	0.13	485	12	0.01	4	389	850	3.61	16	<1	38	<5	<0.01	<10	<10	13	<10	1466	2
83658	>200.0	0.50	764	65	<0.5	<5	1.34	12	10	164	173	4.47	<1	0.18	<10	0.27	822	25	0.01	8	356	1060	4.07	42	1	46	<5	<0.01	<10	<10	27	<10	1687	3
83659	15.2	0.32	214	84	<0.5	<5	2.91	7	9	86	6	3.22	<1	0.20	<10	0.12	1430	18	0.01	4	387	412	3.33	5	1	69	<5	<0.01	<10	<10	19	<10	940	2
83660	4.9	0.42	279	68	<0.5	<5	3.97	4	11	107	8	4.33	<1	0.30	<10	0.10	1184	23	0.01	4	553	367	4.56	6	1	112	<5	<0.01	<10	<10	20	<10	479	3
83661	<0.2	0.99	<5	222	0.6	<5	0.52	<1	7	123	<1	2.02	<1	0.51	<10	0.59	552	<2	0.07	6	666	4	0.01	<5	2	62	5	0.12	<10	<10	39	<10	50	2
83662	>200.0	0.87	1812	94	<0.5	60	4.43	2	61	23	2428	3.10	2	0.09	10	0.25	874	125	0.05	23	856	393	0.66	352	2	146	<5	0.04	<10	<10	24	18	301	8
83663	3.7	1.88	41	204	<0.5	<5	3.92	3	17	25	243	4.86	<1	0.40	11	0.95	2224	12	0.01	3	1330	14	0.92	<5	4	166	5	0.01	<10	<10	63	<10	244	3
83664	3.7	1.87	72	146	0.5	<5	3.35	3	17	24	207	4.44	<1	0.42	10	0.84	1895	18	0.01	2	1318	31	0.72	<5	4	140	<5	0.05	<10	<10	62	<10	222	3
83665	5.5	0.91	139	123	<0.5	<5	7.83	3	12	38	182	3.01	<1	0.34	<10	0.44	2454	14	0.01	2	956	131	1.17	<5	4	219	<5	<0.01	<10	<10	33	<10	356	2
83666	3.1	1.42	67	134	<0.5	<5	4.06	3	15	17	187	4.16	<1	0.38	<10	0.72	2000	15	0.01	2	1092	27	1.07	5	3	141	<5	0.02	<10	<10	49	<10	271	2
83667	1.7	1.86	53	127	0.6	<5	4.27	2	20	21	178	4.42	<1	0.35	11	0.88	2298	13	0.02	3	1273	8	0.55	<5	4	193	<5	0.07	<10	<10	72	<10	192	3
83668	2.3	2.17	54	119	0.5	<5	3.21	2	19	14	185	5.20	<1	0.33	11	1.25	2334	23	0.02	2	1331	29	0.73	<5	4	132	<5	0.08	<10	<10	82	<10	202	3
83669	2.4	1.92	57	139	<0.5	<5	4.29	2	16	22	212	4.94	<1	0.27	10	1.08	2335	14	0.02	3	1193	14	1.09	<5	4	170	<5	0.03	<10	<10	84	<10	198	3
83670	0.3	2.08	23	114	0.5	<5	3.92	2	17	11	55	4.89	<1	0.29	12	1.22	2100	13	0.02	2	1253	10	0.46	<5	4	141	<5	0.06	<10	<10	82	<10	165	3
83671	1.7	1.85	29	104	<0.5	<5	3.57	2	19	17	216	4.78	<1	0.29	10	1.01	1893	26	0.03	3	1314	14	0.86	<5	4	132	<5	0.02	<10	<10	80	<10	231	3
83672	3.1	1.90	29	122	0.5	<5	3.70	2	18	10	286	5.23	<1	0.26	11	1.02	2164	11	0.03	2	1327	10	1.04	<5	5	141	<5	0.04	<10	<10	96	<10	245	3
83673	17.8	1.23	191	89	<0.5	<5	4.74	4	19	31	63	5.74	<1	0.27	<10	0.72	2066	13	0.01	3	1203	187	4.41	6	3	178	<5	0.01	<10	<10	68	<10	409	3
83674	3.7	1.85	51	107	<0.5	<5	3.22	2	19	11	277	5.52	<1	0.28	<10	1.18	2001	19	0.02	2	1112	11	1.98	<5	4	150	<5	<0.01	<10	<10	70	333	208	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Quality Assaying for over 25 Years

Assay Certificate

8V-2376-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 6**
Attn: **Sue Deane**

Jul-16-08

We hereby certify the following assay of 24 core samples submitted Jul-02-08

Sample Name	Au g/tonne	Au-check g/tonne	Ag g/tonne
83690	0.34	0.29	1.5
83691	0.18		1.4
83692	0.15		1.0
83693	0.26		1.1
83694	0.27		0.6
83695	0.22		0.4
83696	0.16		0.6
83697	0.11		1.6
83698	0.02		0.5
83699	0.02	0.02	0.5
83700	0.05		1.5
83701	0.27		5.7
83702	0.09		1.5
83703	0.04		1.1
83704	0.17		20.8
83705	0.15		6.8
83706	0.27		11.7
83707	0.23		8.1
83708	0.32		9.7
83709	0.36	0.32	7.5
83710	0.50		6.0
83711	0.53		6.6
83712	0.66		19.0
83713	0.75		21.5
*0218	0.92		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2376-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 6**
Attn: **Sue Deane**

Jul-16-08

We hereby certify the following assay of 24 core samples submitted Jul-02-08

Sample Name	Au g/tonne	Au-check g/tonne	Ag g/tonne	Pb %	Zn %
83714	2.22	1.98	1008		
83715	3.20		8260	3.59	5.50
83716	1.46		891		1.60
83717	1.25		1103		
83718	2.66		1740	1.07	4.05
83719	0.36		48.7		
83720	0.35		20.0		
83721	<0.01		4.1		
83722	1.77		152.9		
83723	0.27	0.28	8.7		
83724	0.30		17.0		
83725	0.55		6.2		
83726	0.43		6.7		
83727	0.70		7.8		
83728	0.65		8.2		
83729	0.29		5.7		
83730	0.15		1.8		
83731	0.11		2.1		
83732	0.09		1.2		
83733	0.18	0.17	7.0		
83734	0.17		1.8		
83735	0.46		2.5		
83736	0.21		1.6		
83737	0.10		2.1		
*0218	0.90				
*CCu-1c			129.8	0.35	4.04
*KC-1a					
*BLANK	<0.01		<0.1	<0.01	<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2376-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 6**
Attn: **Sue Deane**

Jul-16-08

We hereby certify the following assay of 24 core samples submitted Jul-02-08

Sample Name	Au g/tonne	Au-check g/tonne	Ag g/tonne
83738	0.17	0.16	2.8
83739	0.15		1.8
83740	0.90		11.7
83741	0.10		1.1
83742	0.16		0.8
83743	0.11		2.5
83744	0.08		1.1
83745	0.16		2.5
83746	0.19		1.0
83747	0.16	0.15	0.7
83748	0.18		1.0
83749	0.78		3.3
83750	0.37		3.3
83751	0.64		6.7
83752	0.06		1.1
83753	0.27		2.0
83754	0.06		1.4
83755	0.11		4.3
83756	0.17		16.5
83757	0.32	0.36	4.3
83758	0.45		28.4
83759	0.42		6.7
83760	0.86		30.4
WDR08-01	0.82		22.4
*0218	0.93		
*BLANK	<0.01		

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2376RJ**

Date : Jul-16-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 6

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
83690	1.5	1.81	14	64	<0.5	<5	3.74	2	13	17	170	4.32	<1	0.20	<10	1.08	1640	6	0.02	3	1058	10	0.26	<5	4	101	<5	0.08	<10	24	72	<10	135	4
83691	1.4	1.81	<5	46	<0.5	<5	2.66	2	13	33	224	4.05	<1	0.10	<10	1.29	1468	7	0.04	3	1089	6	0.10	<5	4	86	<5	0.14	<10	29	79	<10	134	4
83692	1.0	1.83	5	61	<0.5	<5	3.10	2	15	11	145	4.23	<1	0.20	<10	1.09	1540	4	0.03	2	1170	5	0.18	<5	4	74	<5	0.14	<10	20	72	<10	118	4
83693	1.1	1.35	25	58	<0.5	<5	2.62	1	10	25	88	3.65	<1	0.21	<10	0.78	1312	6	0.02	2	906	6	0.70	<5	3	34	<5	0.07	<10	27	46	<10	112	3
83694	0.6	1.39	5	66	<0.5	<5	2.44	2	8	24	42	3.45	<1	0.23	<10	0.78	1186	7	0.03	1	851	7	0.37	<5	4	35	<5	0.09	<10	22	40	<10	153	3
83695	0.4	1.41	13	62	<0.5	<5	2.77	1	9	32	37	3.61	<1	0.22	<10	0.81	1226	6	0.02	1	905	10	0.58	<5	4	41	<5	0.07	<10	22	43	<10	120	3
83696	0.6	1.41	26	66	<0.5	<5	2.80	1	8	24	47	3.68	<1	0.21	<10	0.84	1327	6	0.03	2	1101	9	0.78	<5	4	77	<5	0.04	<10	22	49	<10	121	3
83697	1.6	1.49	<5	374	<0.5	5	3.03	1	14	25	297	3.65	<1	0.25	<10	0.72	1308	7	0.03	2	1157	5	0.39	<5	4	105	<5	0.05	<10	24	57	<10	103	3
83698	0.5	2.37	37	159	<0.5	7	3.08	2	12	14	9	5.27	<1	0.25	<10	1.18	1557	<2	0.02	2	1511	8	0.70	<5	3	76	<5	0.03	<10	31	40	<10	97	3
83699	0.5	2.55	49	148	<0.5	7	2.54	2	13	8	9	5.60	<1	0.22	<10	1.30	1622	<2	0.02	2	1678	8	0.55	<5	4	56	<5	0.03	<10	35	48	<10	111	3
83700	1.5	2.11	102	134	<0.5	8	2.43	29	11	8	19	4.94	<1	0.22	<10	1.07	1430	<2	0.02	2	1388	292	1.01	5	3	60	<5	0.02	<10	27	43	<10	3090	3
83701	5.7	1.77	665	112	<0.5	7	1.86	29	12	24	38	5.31	1	0.23	<10	0.88	1281	3	0.02	3	1388	837	2.33	13	2	51	<5	0.04	<10	30	35	<10	3228	3
83702	1.5	1.67	311	155	<0.5	7	1.62	3	11	11	30	4.63	<1	0.24	<10	0.83	1247	3	0.02	2	1378	78	1.42	7	2	33	<5	0.03	<10	25	33	<10	256	3
83703	1.1	2.16	134	146	<0.5	6	1.81	3	13	21	24	5.44	<1	0.22	<10	1.14	1653	2	0.03	3	1632	125	1.39	5	3	47	<5	0.03	<10	26	47	<10	245	4
83704	20.8	1.44	386	42	<0.5	11	0.63	28	13	14	431	6.23	1	0.24	<10	0.71	1052	<2	0.02	2	1282	1055	4.29	24	2	22	<5	0.02	<10	29	29	<10	2862	4
83705	6.8	1.59	273	134	<0.5	7	1.20	9	11	21	75	4.82	<1	0.26	<10	0.77	1395	2	0.02	2	1340	387	2.06	9	2	38	<5	0.05	<10	22	31	<10	1051	3
83706	11.7	0.75	271	39	<0.5	12	0.96	75	9	30	413	6.29	3	0.28	<10	0.25	703	<2	0.02	2	936	2091	>5.00	15	1	47	<5	0.01	<10	29	16	<10	8196	4
83707	8.1	0.79	309	39	<0.5	14	2.50	45	11	45	45	7.11	2	0.31	<10	0.24	1161	3	0.02	3	1081	2256	>5.00	11	1	88	<5	0.01	<10	40	18	<10	4988	4
83708	9.7	0.59	333	54	<0.5	9	0.81	37	10	34	121	5.42	1	0.26	<10	0.20	570	<2	0.01	4	743	1111	>5.00	14	1	53	<5	0.01	<10	25	16	<10	4239	3
83709	7.5	0.99	295	84	<0.5	10	1.39	40	12	52	59	4.97	2	0.29	<10	0.41	1048	<2	0.01	4	876	1754	3.95	13	2	74	<5	0.01	<10	23	28	<10	4935	3
83710	6.0	0.85	342	94	<0.5	10	2.04	13	11	35	47	4.17	<1	0.32	<10	0.27	1110	<2	0.01	3	867	583	3.26	9	2	83	<5	0.01	<10	22	20	<10	1592	3
83711	6.6	0.56	448	115	<0.5	6	0.41	9	8	50	35	2.98	<1	0.29	<10	0.11	369	3	0.01	3	912	367	2.44	9	1	17	<5	<0.01	<10	15	10	<10	1043	2
83712	19.0	0.35	3052	57	<0.5	10	0.08	13	7	63	30	4.64	1	0.21	<10	0.08	184	3	0.01	4	573	1196	4.52	53	1	2	<5	<0.01	<10	19	10	<10	1501	3
83713	21.5	0.22	2766	59	<0.5	10	<0.01	4	5	115	24	4.38	<1	0.14	<10	0.05	135	2	0.01	4	316	187	4.13	57	<1	<1	<5	<0.01	<10	15	7	<10	414	3
83714	>200.0	0.14	802	52	<0.5	10	0.02	37	4	113	328	4.99	1	0.10	<10	0.06	137	<2	0.01	5	283	3473	>5.00	152	<1	1	<5	<0.01	<10	<10	7	<10	6096	3
83715	>200.0	<0.01	1820	10	<0.5	29	<0.01	327	2	136	1326	14.26	8	0.04	24	0.01	56	<2	0.01	5	172	>10000	>5.00	1026	<1	1	<5	<0.01	<10	37	7	<10	>10000	9
83716	>200.0	0.08	1590	18	<0.5	22	<0.01	104	4	144	206	10.61	3	0.10	13	0.03	138	<2	0.01	6	209	5398	>5.00	134	<1	8	<5	<0.01	<10	22	7	<10	>10000	7
83717	>200.0	0.42	834	31	<0.5	14	0.05	61	5	150	107	7.61	2	0.19	<10	0.16	508	2	0.01	6	544	3955	>5.00	96	1	6	<5	<0.01	<10	18	15	<10	9467	5
83718	>200.0	<0.01	2090	<10	<0.5	31	<0.01	250	3	174	253	>15.00	6	0.04	11	0.01	120	<2	<0.01	6	137	>10000	>5.00	279	<1	4	<5	<0.01	<10	50	8	<10	>10000	10
83719	48.7	0.27	637	63	<0.5	7	0.04	6	5	175	28	4.15	1	0.15	11	0.09	253	4	0.01	6	277	405	3.93	28	<1	5	<5	<0.01	<10	<10	7	<10	823	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

Ascot Resources Ltd

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Report No : 8V2376RJ

Attention: Sue Deane

Tel: (604) 327-3436 Fax: (604) 327-3423

Date : Jul-16-08

Project: Dilworth/Shipment 6

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
83720	20.0	0.39	306	73	<0.5	<5	1.06	5	4	138	25	1.82	<1	0.15	<10	0.18	800	2	0.01	4	343	241	1.16	14	1	39	<5	<0.01	<10	<10	12	<10	685	2
83721	4.1	1.02	<5	226	<0.5	<5	0.51	1	6	172	1	2.01	<1	0.48	11	0.60	544	2	0.08	8	723	21	0.03	5	2	69	<5	0.15	<10	<10	37	<10	72	3
83722	152.9	0.82	202	190	<0.5	93	5.09	2	15	20	3607	3.42	4	0.17	<10	0.17	606	73	0.03	31	616	195	1.20	243	2	170	<5	0.07	<10	<10	21	21	232	11
83723	8.7	0.82	236	115	<0.5	<5	0.66	1	6	98	42	2.33	<1	0.19	<10	0.47	1114	2	0.01	4	610	26	0.77	12	1	45	<5	<0.01	<10	<10	33	<10	66	2
83724	17.0	0.67	253	95	<0.5	<5	0.52	7	8	92	30	3.26	<1	0.16	<10	0.47	960	2	0.01	6	660	193	2.09	14	1	34	<5	<0.01	<10	12	27	<10	910	3
83725	6.2	1.12	222	132	<0.5	5	1.72	6	9	52	31	3.94	<1	0.22	<10	0.67	1808	<2	0.01	4	855	104	1.93	7	2	60	<5	<0.01	<10	19	49	<10	798	3
83726	6.7	1.18	250	130	<0.5	<5	1.86	5	9	64	33	3.43	<1	0.29	<10	0.62	1614	2	0.01	4	892	79	1.36	7	2	88	<5	0.01	<10	10	39	<10	535	3
83727	7.8	0.77	474	117	<0.5	5	5.31	4	7	47	20	2.87	<1	0.19	<10	0.40	1854	4	0.01	3	641	70	1.66	9	2	183	<5	<0.01	<10	17	34	<10	492	2
83728	8.2	1.16	300	99	<0.5	5	8.94	2	13	35	58	3.95	<1	0.20	<10	0.62	3371	3	0.01	5	767	45	1.88	8	3	206	<5	0.01	<10	27	57	<10	114	3
83729	5.7	2.20	309	155	<0.5	6	4.37	3	22	24	116	5.91	<1	0.23	<10	1.54	3180	<2	0.01	14	847	213	2.02	7	6	150	<5	0.01	<10	31	149	<10	271	4
83730	1.8	1.99	195	169	<0.5	8	2.08	2	21	12	34	5.24	<1	0.44	<10	0.91	2057	<2	0.01	4	1450	30	1.57	<5	4	69	<5	0.01	<10	10	84	<10	100	4
83731	2.1	1.88	111	133	<0.5	<5	4.15	2	15	7	47	4.57	<1	0.40	<10	0.88	2421	<2	0.01	4	1259	73	1.05	<5	3	117	<5	<0.01	<10	15	62	<10	95	3
83732	1.2	1.67	86	161	<0.5	6	5.28	2	15	13	552	4.16	<1	0.44	<10	0.68	2018	<2	0.01	3	1267	13	1.28	<5	4	132	<5	0.01	<10	16	57	<10	79	3
83733	7.0	1.52	240	114	<0.5	8	3.10	2	22	8	922	5.34	<1	0.47	<10	0.75	1400	2	0.01	4	1469	30	3.45	6	4	87	<5	0.01	<10	22	48	<10	87	4
83734	1.8	1.45	268	105	<0.5	6	3.80	3	19	11	120	4.99	<1	0.37	<10	0.76	1619	<2	0.01	4	1226	25	2.76	5	3	108	<5	<0.01	<10	22	37	<10	148	3
83735	2.5	1.14	531	80	<0.5	8	2.13	3	22	12	138	5.26	<1	0.41	<10	0.58	1045	<2	0.01	5	1321	38	4.24	7	3	63	<5	<0.01	<10	20	30	<10	99	4
83736	1.6	1.32	354	92	<0.5	7	4.17	3	22	11	58	5.77	<1	0.35	<10	0.77	1659	<2	0.01	4	1486	41	4.24	<5	3	117	<5	0.01	<10	23	34	<10	98	4
83737	2.1	1.34	165	113	<0.5	6	9.70	2	15	10	85	4.47	<1	0.33	<10	0.72	2482	2	0.01	3	1150	37	2.66	5	2	220	<5	<0.01	<10	25	32	<10	97	3
83738	2.8	1.12	172	122	<0.5	6	7.60	3	11	26	70	3.68	<1	0.31	<10	0.47	2434	3	0.01	3	1000	50	2.07	6	2	156	<5	0.02	<10	34	26	<10	236	3
83739	1.8	1.94	2173	103	<0.5	5	5.54	5	13	8	74	4.95	<1	0.24	<10	1.12	2502	3	0.02	3	1286	95	0.89	5	3	136	<5	<0.01	<10	35	69	<10	332	3
83740	11.7	1.21	>10000	79	<0.5	9	9.28	98	9	21	269	5.49	<1	0.16	<10	0.68	3916	<2	0.02	2	868	707	3.49	10	2	208	<5	<0.01	<10	40	52	<10	8629	3
83741	1.1	1.65	218	104	<0.5	5	5.29	2	12	12	42	4.42	<1	0.23	<10	0.91	2220	<2	0.02	2	1136	18	1.25	<5	3	113	<5	0.01	<10	32	67	<10	62	3
83742	0.8	1.45	143	120	<0.5	5	7.20	2	11	24	31	3.88	<1	0.32	<10	0.73	2191	2	0.02	3	1240	58	1.41	<5	3	180	<5	0.04	<10	28	47	<10	90	3
83743	2.5	1.54	195	126	<0.5	5	5.57	2	13	10	36	4.44	<1	0.35	<10	0.76	2091	<2	0.02	2	1232	55	1.81	<5	2	137	<5	0.03	<10	36	46	<10	67	3
83744	1.1	1.94	185	110	<0.5	8	3.37	2	18	14	24	5.55	<1	0.28	<10	1.14	2153	<2	0.01	3	1357	33	2.08	<5	2	96	<5	0.03	<10	38	65	<10	53	4
83745	2.5	0.68	228	103	<0.5	<5	10.06	2	10	22	95	3.40	<1	0.27	<10	0.29	2601	<2	0.01	2	843	86	2.86	6	2	228	<5	0.03	<10	35	22	<10	120	2
83746	1.0	0.33	494	77	<0.5	<5	6.84	1	6	68	14	1.75	<1	0.19	<10	0.11	2073	3	0.01	2	486	32	1.47	8	1	161	<5	0.01	<10	24	10	<10	54	1
83747	0.7	0.45	379	87	<0.5	<5	4.43	1	7	74	22	1.79	<1	0.18	<10	0.20	1415	2	0.01	3	528	21	1.10	8	1	160	<5	0.02	<10	24	16	<10	134	2
83748	1.0	1.04	123	100	<0.5	<5	6.96	1	11	46	56	2.89	<1	0.30	<10	0.50	2285	8	0.01	2	926	36	1.25	<5	2	272	<5	0.04	<10	27	31	<10	103	2
83749	3.3	0.49	206	84	<0.5	6	6.40	4	8	47	138	2.73	<1	0.20	<10	0.24	1844	10	0.01	2	544	129	2.28	<5	1	154	<5	0.01	<10	32	17	<10	372	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2376RJ

Date : Jul-16-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 6

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
83750	3.3	0.67	224	83	<0.5	5	6.21	2	9	59	124	3.07	<1	0.24	<10	0.33	1893	77	0.01	2	606	316	2.34	<5	1	142	<5	0.03	<10	39	19	<10	193	2
83751	6.7	1.75	83	103	<0.5	<5	3.94	9	16	15	372	4.77	<1	0.30	<10	1.04	2019	29	0.01	2	1156	751	1.64	<5	3	128	5	0.08	<10	41	59	<10	1064	3
83752	1.1	2.29	25	107	<0.5	<5	4.08	3	17	20	108	5.12	<1	0.34	<10	1.42	2096	16	0.02	2	1304	46	0.85	<5	3	171	5	0.12	<10	38	63	<10	252	4
83753	2.0	1.49	211	134	<0.5	5	5.04	3	16	17	123	4.71	<1	0.40	<10	0.73	1845	25	0.01	1	1254	63	2.53	<5	2	265	6	0.06	<10	41	32	<10	230	3
83754	1.4	2.10	136	194	<0.5	8	1.63	2	13	23	28	5.20	<1	0.25	<10	1.02	1322	3	0.02	2	1523	53	1.28	<5	3	33	6	0.01	<10	34	37	<10	134	3
83755	4.3	1.54	252	152	<0.5	5	2.36	10	12	26	27	4.81	<1	0.25	<10	0.70	1535	<2	0.02	2	1301	498	2.41	7	2	85	5	0.06	<10	39	31	<10	1214	3
83756	16.5	1.07	339	57	<0.5	12	0.92	43	11	52	213	6.71	1	0.27	<10	0.43	872	<2	0.01	3	975	2090	>5.00	13	1	26	<5	0.01	<10	49	23	<10	4946	4
83757	4.3	1.03	360	156	<0.5	8	1.41	4	12	35	38	3.98	<1	0.29	<10	0.39	1000	<2	0.01	4	953	290	2.52	7	2	54	6	0.01	<10	40	24	<10	547	3
83758	28.4	0.43	642	106	<0.5	8	0.44	21	8	84	47	3.46	<1	0.27	<10	0.08	284	3	0.01	5	677	2670	3.42	20	1	11	<5	<0.01	<10	39	8	<10	2564	2
83759	6.7	0.43	3251	150	<0.5	5	0.40	4	7	75	34	2.27	<1	0.19	<10	0.16	441	2	0.01	4	618	179	1.56	77	1	13	5	<0.01	<10	33	13	<10	561	2
83760	30.4	0.11	3508	77	<0.5	5	2.06	10	3	124	40	2.18	<1	0.09	<10	0.02	719	3	0.01	4	216	531	2.08	81	<1	36	<5	<0.01	14	38	3	<10	1689	1
WDR08-01	22.4	0.38	497	70	<0.5	13	0.02	11	4	98	149	6.88	<1	0.19	<10	0.19	340	45	0.01	3	530	4448	3.47	21	<1	<1	<5	0.02	<10	51	18	<10	1232	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Quality Assaying for over 25 Years

Assay Certificate

8V-2415-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 6**
Attn: **Sue Deane**

Jul-18-08

We hereby certify the following assay of 24 core samples submitted Jul-04-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %	Zn %
83761	0.68	0.69	28.5		
83762	1.97		2195	1.83	3.28
83763	0.80		62.5		
83764	0.25		13.1		
83765	0.30		10.0		
83766	0.29		4.2		
83767	0.30		4.2		
83768	0.28		5.1		
83769	0.26		2.9		
83770	0.31	0.29	3.0		
83771	0.09		2.0		
83772	0.07		1.3		
83773	0.33		1.2		
83774	0.05		1.2		
83775	0.04		0.8		
83776	0.02		0.8		
83777	0.06		0.9		
83778	0.18		1.0		
83779	0.03		0.8		
83780	0.03	0.04	0.5		
83780A	0.02		0.5		
83780B	0.17		6.4		
83781	0.01		0.7		
83782	<0.01		0.5		
*0218	0.93				
*CCu-1c			132	0.35	3.93
*BLANK	<0.01		<0.1	<0.01	<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2415-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 6**
Attn: **Sue Deane**

Jul-18-08

We hereby certify the following assay of 24 core samples submitted Jul-04-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
83783	0.05	0.05	1.1
83784	0.04		1.2
83785	0.02		0.6
83786	0.19		20.1
83787	0.06		0.8
83788	0.18		10.5
83789	0.42		16.7
83790	2.13		14.5
83791	0.27		4.4
83792	0.38	0.39	5.5
83793	0.32		4.3
83794	0.27		5.2
83795	0.24		2.3
83796	<0.01		0.3
83797	1.25		235.0
83798	0.11		8.1
83799	0.25		12.5
83800	0.19		2.9
83801	0.13		5.1
83802	0.18	0.19	17.2
83803	0.10		2.7
83804	0.14		9.1
83805	0.24		3.9
83806	0.16		3.1
*0218	0.88		
*CCu-1c			130.2
*BLANK	<0.01		<0.1

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2415-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 6**
Attn: **Sue Deane**

Jul-18-08

We hereby certify the following assay of 24 core samples submitted Jul-04-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
83807	0.10	0.10	4.8
83808	0.91		4.8
83809	0.07		2.5
83810	0.67		172.2
83811	0.40		4.4
83812	0.14		5.6
83813	0.01		0.8
83814	0.40		1.7
83815	0.49		2.0
83816	0.36	0.30	1.6
83817	0.09		1.5
83818	0.09		1.9
83819	0.26		2.2
83820	0.35		2.1
83821	0.53		7.4
83822	0.44		3.7
83823	0.44		1.9
83824	0.66		1.1
83825	0.50		1.1
83826	0.07	0.07	0.8
83827	0.07		2.6
83828	0.12		3.1
83829	0.15		8.1
83830	0.14		1.1
*0218	0.90		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2415-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 6**
Attn: **Sue Deane**

Jul-18-08

We hereby certify the following assay of 24 core samples submitted Jul-04-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
83831	0.02	0.02	0.3
83832	0.08		1.0
83833	0.04		0.8
83834	0.08		2.3
83835	0.51		2.9
83836	0.09		1.0
83837	0.02		0.3
83838	0.01		0.2
83839	0.02		0.3
83840	0.01	<0.01	0.2
83841	0.01		0.6
83842	<0.01		<0.1
83843	0.01		0.3
83844	0.02		0.9
83845	0.11		1.1
83846	0.01		1.6
83847	0.01		<0.1
83848	0.04		2.1
83849	0.03		2.5
83850	0.03	0.03	3.6
83851	0.02		1.1
83852	0.04		1.7
83853	0.38		3.8
83854	0.11		2.4
*0218	0.86		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2415-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 6**
Attn: **Sue Deane**

Jul-18-08

We hereby certify the following assay of 24 core samples submitted Jul-04-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
83855	0.07	0.08	2.0	
83856	0.07		1.0	
83857	0.09		1.1	
83858	0.09		1.1	
83859	0.16		3.5	
83860	0.39		6.7	
83861	0.05		1.6	
83862	0.06		1.4	
83863	0.05		1.5	
83864	0.05	0.05	2.0	
83865	0.02		1.4	
83866	0.05		1.0	
83867	0.10		6.1	
83868	0.32		4.5	
83869	0.13		13.1	
83870	0.12		10.7	
83871	0.12		8.0	
83872	0.26		10.7	
83873	2.12		20.1	
83874	0.70	0.72	12.3	
WDR08-02	0.14		10.5	
WDR08-03	0.02		1.4	
SP08-01	87.40		4170	2.10
*0218	0.93			
*CCu-1c			132	3.93
*BLANK	<0.01		<0.1	<0.01

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2415RJ**

Date : Jul-18-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 6

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
83761	28.5	0.11	2346	56	<0.5	5	0.40	7	3	91	32	2.89	<1	0.10	<10	0.02	190	<2	<0.01	3	222	424	2.80	41	<1	10	<5	<0.01	<10	13	4	<10	892	2
83762	>200.0	<0.01	2035	15	<0.5	31	0.07	206	2	95	800	>15.00	5	0.06	<10	0.02	152	<2	<0.01	1	192	>10000	>5.00	540	<1	9	<5	<0.01	<10	60	8	<10	>10000	10
83763	62.5	0.34	843	41	<0.5	10	0.41	12	6	91	62	4.81	<1	0.16	<10	0.11	476	2	0.01	3	420	591	4.62	38	1	19	<5	<0.01	<10	13	11	<10	1636	3
83764	13.1	0.39	239	79	<0.5	<5	2.51	3	5	105	20	2.20	<1	0.15	<10	0.17	1093	3	0.01	4	411	422	1.54	13	1	58	<5	<0.01	<10	11	10	<10	358	2
83765	10.0	0.73	432	86	<0.5	<5	0.88	1	6	65	27	3.17	<1	0.20	<10	0.38	1013	2	0.01	3	677	67	1.88	24	1	26	<5	0.01	<10	13	24	<10	92	3
83766	4.2	0.79	141	86	<0.5	<5	6.46	2	5	46	26	2.49	<1	0.15	<10	0.47	2408	<2	0.01	2	586	67	1.00	9	2	114	<5	0.01	<10	17	32	<10	212	2
83767	4.2	0.91	320	102	<0.5	<5	0.68	3	8	40	21	3.45	<1	0.19	<10	0.53	1396	3	0.01	2	740	90	1.83	9	2	34	<5	0.02	<10	13	47	<10	283	3
83768	5.1	1.53	231	91	<0.5	5	1.76	2	15	24	112	4.93	<1	0.14	<10	0.97	2550	3	0.01	4	886	49	1.84	7	5	65	<5	0.03	<10	24	113	<10	94	3
83769	2.9	1.87	235	94	<0.5	6	1.97	2	18	11	100	5.53	<1	0.19	<10	1.06	2586	5	0.01	4	1037	32	1.71	5	5	77	<5	0.01	<10	27	116	<10	66	3
83770	3.0	1.53	419	74	<0.5	7	1.78	2	18	13	42	5.55	<1	0.17	<10	0.99	2039	<2	0.01	5	840	34	2.70	5	4	68	<5	0.01	<10	27	113	<10	95	3
83771	2.0	1.61	135	135	<0.5	6	2.96	2	20	13	59	4.55	<1	0.33	<10	0.77	1885	<2	0.01	4	1100	34	1.43	<5	3	70	<5	<0.01	<10	21	57	<10	110	3
83772	1.3	1.37	86	107	<0.5	7	2.45	1	17	6	51	4.09	<1	0.39	<10	0.53	1233	<2	0.01	3	1284	14	1.62	<5	3	56	<5	<0.01	<10	16	46	<10	58	3
83773	1.2	1.04	423	82	<0.5	5	4.61	2	17	10	41	4.51	<1	0.35	<10	0.44	1324	<2	0.01	2	1319	19	3.28	8	3	118	<5	0.01	<10	23	34	<10	78	3
83774	1.2	1.54	101	113	<0.5	5	4.94	2	18	6	46	4.25	<1	0.29	<10	0.76	1566	<2	0.01	3	1246	16	1.66	<5	4	124	<5	0.01	<10	32	51	<10	83	2
83775	0.8	1.27	97	87	<0.5	5	3.82	2	16	13	39	4.48	<1	0.32	<10	0.63	1302	<2	0.01	1	1334	27	2.65	<5	3	104	<5	0.01	<10	17	34	<10	56	3
83776	0.8	1.51	72	87	<0.5	6	4.17	2	18	6	38	4.81	<1	0.33	<10	0.84	1605	<2	0.01	2	1324	34	2.79	<5	3	104	<5	0.01	<10	24	37	<10	59	3
83777	0.9	1.28	135	61	<0.5	7	3.93	3	21	19	43	5.37	<1	0.34	<10	0.70	1499	<2	0.01	3	1368	38	4.07	6	3	103	<5	0.02	<10	25	36	<10	73	4
83778	1.0	0.72	269	65	<0.5	6	3.98	2	14	11	30	3.86	<1	0.30	<10	0.29	1217	2	0.01	2	1146	40	3.31	7	2	103	<5	0.02	<10	18	17	<10	75	3
83779	0.8	1.49	106	91	<0.5	<5	4.90	2	12	10	24	4.46	<1	0.25	<10	0.81	1725	<2	0.01	1	1203	34	1.88	5	2	103	<5	<0.01	<10	23	34	<10	61	3
83780	0.5	1.68	67	98	<0.5	<5	4.40	2	12	7	24	4.33	<1	0.23	<10	0.93	2014	<2	0.02	2	1255	25	1.11	<5	2	108	<5	<0.01	<10	24	53	<10	62	3
83780A	0.5	1.78	71	85	<0.5	<5	3.93	1	12	11	23	4.27	<1	0.19	<10	1.09	2130	<2	0.02	1	1263	23	0.67	<5	3	98	<5	0.01	<10	20	57	<10	73	3
83780B	6.4	1.88	1156	85	<0.5	<5	3.00	47	12	6	67	4.51	<1	0.23	<10	1.11	1880	<2	0.02	2	1264	1016	0.93	8	2	81	<5	0.01	<10	21	55	<10	4004	3
83781	0.7	2.21	170	130	<0.5	<5	2.12	2	12	13	8	5.01	<1	0.20	<10	1.07	1273	2	0.02	1	1413	13	0.53	5	3	53	<5	0.01	<10	18	40	<10	130	3
83782	0.5	2.13	26	109	<0.5	<5	4.99	4	10	6	28	4.79	<1	0.19	<10	1.06	1761	2	0.02	1	1444	76	0.65	<5	3	124	<5	0.02	<10	22	42	<10	275	3
83783	1.1	2.36	23	103	<0.5	5	2.64	5	12	8	16	5.13	<1	0.17	<10	1.23	1540	2	0.01	2	1324	193	0.47	5	3	62	5	0.02	<10	29	42	<10	477	3
83784	1.2	2.14	85	109	<0.5	5	2.40	2	12	11	10	5.18	<1	0.19	<10	1.11	1410	<2	0.01	2	1330	25	1.13	5	3	60	5	0.02	<10	26	40	<10	123	3
83785	0.6	2.45	36	99	<0.5	<5	2.82	2	13	6	2	5.47	<1	0.15	<10	1.35	1750	<2	0.02	2	1398	11	0.75	<5	4	72	5	0.05	<10	29	57	<10	130	3
83786	20.1	1.10	309	47	<0.5	7	3.36	28	13	19	538	5.60	<1	0.21	<10	0.51	1397	<2	0.01	2	1128	1765	4.98	17	2	98	<5	0.06	<10	24	22	<10	3257	3
83787	0.8	2.20	89	128	<0.5	5	1.23	2	14	8	8	5.48	<1	0.22	<10	1.17	1434	<2	0.01	2	1469	29	1.46	5	3	37	5	0.07	<10	21	46	<10	126	3
83788	10.5	0.84	277	45	<0.5	5	1.32	15	11	23	388	4.30	<1	0.22	<10	0.34	692	<2	0.01	2	952	768	3.42	12	2	54	6	0.02	<10	24	18	<10	1632	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2415RJ**

Date : Jul-18-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 6

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
83789	16.7	0.33	386	91	<0.5	<5	0.89	12	6	49	92	2.91	<1	0.17	<10	0.08	406	3	0.01	2	423	568	2.53	18	1	17	5	<0.01	13	18	6	<10	1407	2
83790	14.5	0.14	391	42	<0.5	7	0.09	27	5	81	119	3.97	<1	0.12	<10	0.02	71	3	0.01	2	230	876	4.22	18	<1	<1	6	<0.01	<10	22	3	<10	3297	2
83791	4.4	0.43	212	74	<0.5	6	0.46	13	9	54	52	3.54	<1	0.19	<10	0.17	399	2	0.01	3	576	437	3.15	11	1	9	6	<0.01	10	21	9	<10	1630	2
83792	5.5	0.52	320	69	<0.5	6	0.77	3	9	44	22	3.68	<1	0.25	<10	0.16	449	3	0.01	3	782	104	3.27	16	1	15	6	<0.01	12	20	12	<10	390	2
83793	4.3	0.64	279	91	<0.5	6	0.49	4	10	37	17	3.37	<1	0.27	<10	0.21	460	3	0.01	3	819	238	2.60	13	1	<1	7	<0.01	20	20	15	<10	486	2
83794	5.2	0.49	274	62	<0.5	7	0.28	5	10	50	12	3.78	<1	0.23	<10	0.17	266	4	0.01	3	724	194	3.56	15	1	<1	8	<0.01	18	23	13	<10	586	2
83795	2.3	0.87	87	97	<0.5	<5	1.27	1	7	55	1	3.03	<1	0.16	<10	0.57	1133	<2	0.01	3	660	76	1.56	6	2	13	7	<0.01	18	25	30	<10	145	2
83796	0.3	0.88	<5	209	<0.5	<5	0.44	<1	6	98	<1	1.83	<1	0.44	<10	0.53	500	<2	0.06	5	655	<2	0.01	<5	2	33	11	0.12	38	18	34	<10	43	2
83797 (pulp)	>200.0	0.75	1719	81	<0.5	54	3.84	2	52	20	2097	2.68	1	0.08	<10	0.21	762	125	0.05	20	751	327	0.59	409	2	109	7	0.03	26	24	17	15	258	7
83798	8.1	0.50	58	58	<0.5	<5	3.83	1	4	44	2	1.91	<1	0.10	<10	0.32	1453	<2	0.01	2	385	174	0.97	6	1	49	7	<0.01	25	26	21	<10	136	1
83799	12.5	0.57	410	79	<0.5	<5	3.21	2	7	68	19	2.40	<1	0.11	<10	0.31	1753	2	0.01	3	368	166	1.42	12	1	52	7	<0.01	22	29	36	<10	211	1
83800	2.9	2.21	56	96	<0.5	5	2.69	2	18	11	102	5.31	<1	0.18	<10	1.51	3013	<2	0.01	5	916	33	1.36	6	6	75	8	0.01	<10	42	138	<10	130	3
83801	5.1	2.02	84	97	<0.5	6	1.80	2	19	15	95	5.01	<1	0.19	<10	1.31	2598	<2	0.01	5	888	74	1.27	6	4	48	8	0.01	12	41	110	<10	89	3
83802	17.2	2.36	56	82	<0.5	6	2.26	3	20	6	104	5.37	<1	0.21	<10	1.54	2618	<2	0.01	6	930	80	1.00	7	5	54	8	0.01	10	44	107	<10	305	3
83803	2.7	2.22	103	72	<0.5	6	2.22	2	20	8	85	5.36	<1	0.26	<10	1.36	2699	<2	0.01	5	935	24	1.33	5	4	51	8	0.01	<10	43	89	<10	128	3
83804	9.1	1.47	89	84	<0.5	5	3.03	2	16	11	66	3.89	<1	0.27	<10	0.80	2343	<2	0.01	4	851	96	1.40	6	3	69	8	<0.01	18	35	51	<10	123	2
83805	3.9	1.42	80	85	<0.5	5	2.76	9	16	14	111	3.96	<1	0.27	<10	0.72	2103	<2	0.01	5	849	137	1.45	5	3	58	8	<0.01	19	35	43	<10	1029	2
83806	3.1	1.44	452	96	<0.5	6	2.54	5	15	14	79	4.18	<1	0.29	<10	0.73	2000	<2	0.01	5	953	93	1.72	6	3	70	8	<0.01	15	33	47	<10	468	2
83807	4.8	2.02	176	113	<0.5	7	2.31	3	17	14	106	5.76	<1	0.26	<10	1.25	2841	<2	0.01	4	1086	212	2.11	8	5	84	<5	0.01	<10	32	108	<10	215	3
83808	4.8	2.11	248	85	<0.5	<5	2.12	10	15	18	99	5.46	<1	0.19	<10	1.47	2604	5	0.01	3	1011	238	1.67	<5	5	72	<5	0.02	<10	29	114	<10	1209	3
83809	2.5	2.96	122	104	<0.5	<5	2.17	3	21	8	114	6.41	<1	0.22	<10	2.26	3377	<2	0.01	4	1374	42	0.86	<5	7	87	<5	0.03	<10	28	188	<10	108	4
83810	172.2	2.06	342	93	<0.5	<5	2.30	7	17	17	151	5.41	<1	0.23	<10	1.41	2509	<2	0.01	4	1038	422	1.69	15	5	62	<5	0.01	<10	25	122	<10	859	3
83811	4.4	2.48	62	90	<0.5	6	3.07	8	20	4	161	5.91	<1	0.20	<10	1.76	2605	<2	0.02	4	1199	423	1.15	<5	6	175	<5	0.01	<10	32	139	<10	817	4
83812	5.6	2.21	54	79	<0.5	<5	4.01	2	21	8	87	5.56	<1	0.18	<10	1.65	2941	<2	0.02	4	1178	49	1.65	<5	7	126	<5	0.12	<10	29	137	<10	130	4
83813	0.8	2.33	12	159	<0.5	<5	4.69	2	20	3	75	5.31	<1	0.30	<10	1.47	2094	<2	0.01	4	1208	34	1.16	<5	4	185	<5	0.02	<10	24	74	<10	82	3
83814	1.7	1.42	345	61	<0.5	7	4.40	2	21	11	59	5.49	<1	0.32	<10	0.86	1846	<2	0.01	5	1156	47	3.95	6	3	178	<5	0.01	<10	26	60	<10	76	3
83815	2.0	1.39	525	59	<0.5	8	3.40	3	26	25	58	6.74	<1	0.34	<10	0.99	1389	<2	0.01	6	1515	39	>5.00	8	3	126	<5	0.02	<10	27	55	<10	69	4
83816	1.6	1.56	298	69	<0.5	<5	4.24	2	23	12	86	5.88	<1	0.32	<10	1.07	1657	<2	0.01	6	1238	38	4.40	7	4	172	<5	0.01	<10	27	57	<10	67	4
83817	1.5	2.86	50	113	<0.5	<5	2.92	2	28	31	101	5.58	<1	0.27	<10	2.16	2152	2	0.01	19	916	44	0.54	<5	7	93	<5	0.01	<10	27	116	<10	107	3
83818	1.9	2.22	63	169	<0.5	<5	3.53	2	23	14	94	5.07	<1	0.38	<10	1.07	2131	13	0.01	7	1166	36	0.80	5	5	101	<5	0.01	<10	22	79	<10	141	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2415RJ

Date : Jul-18-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 6

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
83819	2.2	1.83	50	122	<0.5	5	3.47	13	14	9	109	4.37	<1	0.32	10	0.80	2180	36	0.01	2	1267	46	0.71	<5	2	103	<5	0.01	<10	24	40	<10	521	3
83820	2.1	1.70	171	119	<0.5	<5	4.21	15	13	8	95	4.30	<1	0.33	<10	0.75	2399	21	0.01	2	1309	41	1.09	<5	2	139	<5	0.01	<10	22	33	<10	696	3
83821	7.4	1.70	123	140	<0.5	<5	2.76	31	14	10	269	4.45	<1	0.34	<10	0.69	2030	16	0.01	2	1278	110	1.01	<5	2	77	<5	0.04	<10	19	40	<10	1253	3
83822	3.7	1.48	96	161	<0.5	5	1.58	3	11	12	180	3.74	<1	0.33	<10	0.55	1406	34	0.01	1	1329	36	0.60	<5	2	51	<5	<0.01	<10	16	30	<10	288	2
83823	1.9	2.09	40	109	<0.5	<5	5.51	3	16	11	287	5.18	<1	0.33	<10	0.97	1939	56	0.02	1	1339	33	0.73	<5	4	119	<5	0.08	<10	23	63	<10	286	4
83824	1.1	1.95	<5	85	<0.5	<5	4.14	3	15	7	179	4.44	<1	0.28	<10	0.95	1592	55	0.02	1	1244	12	0.26	<5	4	100	<5	0.12	<10	23	64	<10	307	3
83825	1.1	2.10	<5	54	<0.5	<5	2.96	2	16	11	197	4.72	<1	0.13	<10	1.22	1769	76	0.03	1	1240	12	0.22	<5	4	114	<5	0.10	<10	24	72	<10	264	4
83826	0.8	0.67	103	116	<0.5	<5	1.37	1	9	19	8	2.99	<1	0.28	<10	0.28	897	2	0.01	3	910	9	1.79	<5	1	40	<5	<0.01	<10	16	15	<10	39	2
83827	2.6	0.38	124	121	<0.5	<5	6.63	2	7	26	10	2.77	<1	0.24	<10	0.31	2613	2	0.01	2	665	109	1.57	5	2	196	<5	<0.01	<10	21	8	<10	132	2
83828	3.1	0.61	201	134	<0.5	<5	8.50	1	8	16	7	2.56	<1	0.34	<10	0.30	2731	<2	0.01	1	752	24	1.41	<5	2	183	<5	<0.01	12	23	12	<10	40	2
83829	8.1	1.50	619	128	<0.5	<5	3.36	2	10	19	27	3.48	<1	0.31	<10	0.80	2196	<2	0.01	3	1053	55	0.46	10	3	123	<5	<0.01	<10	21	42	<10	125	3
83830	1.1	1.46	123	133	<0.5	<5	3.77	1	11	12	17	3.17	<1	0.39	<10	0.67	2013	<2	0.01	2	1084	9	0.58	5	3	98	<5	0.03	10	16	36	<10	57	3
83831	0.3	1.67	29	140	<0.5	<5	3.13	1	9	8	20	3.52	<1	0.35	10	0.86	1811	<2	0.02	2	1099	3	0.18	<5	3	122	<5	0.01	<10	<10	41	<10	58	3
83832	1.0	1.42	92	137	<0.5	<5	1.09	1	10	23	16	3.66	<1	0.30	<10	0.69	1343	<2	0.01	3	1003	8	0.83	<5	2	43	<5	0.01	<10	<10	44	<10	40	3
83833	0.8	1.50	68	141	<0.5	<5	1.06	1	11	11	14	3.62	<1	0.39	<10	0.66	1320	<2	0.01	2	1050	5	0.78	5	2	28	<5	0.05	<10	<10	38	<10	44	3
83834	2.3	1.38	333	130	<0.5	<5	0.72	1	12	21	18	3.30	<1	0.38	<10	0.63	1157	<2	0.01	3	1094	5	0.94	13	2	29	<5	0.04	<10	<10	40	<10	67	3
83835	2.9	1.27	170	129	<0.5	<5	0.98	1	10	17	23	3.39	<1	0.34	<10	0.54	1187	<2	0.01	3	959	18	1.14	11	2	35	<5	0.02	<10	<10	33	<10	62	3
83836	1.0	1.67	92	135	<0.5	<5	2.71	1	11	15	16	4.35	<1	0.33	<10	0.76	1949	<2	0.01	3	1070	13	1.23	7	2	69	<5	0.02	<10	<10	33	<10	64	3
83837	0.3	1.85	14	136	<0.5	<5	3.44	1	10	10	21	4.19	<1	0.31	<10	0.85	1713	<2	0.02	2	1108	6	0.43	<5	2	88	<5	<0.01	<10	<10	32	<10	67	3
83838	0.2	2.27	7	147	<0.5	<5	1.96	2	16	5	20	5.13	<1	0.36	<10	1.01	1611	<2	0.01	3	1225	11	0.45	<5	2	68	<5	0.02	<10	13	39	<10	70	3
83839	0.3	1.95	16	145	<0.5	<5	3.13	1	13	5	26	4.46	<1	0.37	<10	0.89	1765	<2	0.01	3	1200	21	0.81	<5	2	99	<5	0.06	<10	12	34	<10	69	3
83840	0.2	1.58	9	143	<0.5	<5	3.82	1	13	5	56	3.77	<1	0.38	<10	0.61	1095	<2	0.01	2	1176	11	0.81	<5	2	119	<5	0.06	<10	<10	32	<10	28	3
83841	0.6	1.84	20	161	<0.5	<5	5.77	1	15	5	76	4.26	<1	0.40	<10	0.79	1671	<2	0.01	3	1148	11	0.81	5	4	186	<5	0.01	<10	13	57	<10	41	3
83842	<0.2	2.42	<5	139	<0.5	<5	5.52	2	12	7	133	4.97	<1	0.36	<10	1.35	1504	<2	0.01	4	1221	3	0.31	<5	6	194	<5	0.02	<10	17	90	<10	51	4
83843	0.3	2.12	19	128	<0.5	<5	4.99	2	19	4	77	5.11	<1	0.31	<10	1.07	1564	<2	0.01	4	1150	2	0.70	<5	5	172	<5	0.01	<10	14	69	<10	48	3
83844	0.9	2.24	32	113	<0.5	7	4.37	2	20	3	94	5.51	<1	0.29	<10	1.14	2128	<2	0.01	5	1157	3	0.93	6	4	140	<5	0.01	<10	19	84	<10	42	3
83845	1.1	1.99	62	114	<0.5	<5	4.23	2	21	6	84	5.48	<1	0.25	<10	1.00	2125	<2	0.01	4	1131	4	1.39	<5	4	150	<5	<0.01	<10	21	71	<10	35	4
83846	1.6	1.68	36	128	<0.5	<5	5.46	1	20	3	178	4.27	<1	0.33	<10	1.08	1953	<2	0.01	4	1254	5	0.52	<5	5	232	<5	<0.01	<10	15	47	<10	56	3
83847	<0.2	0.36	6	114	<0.5	<5	12.96	1	3	64	<1	3.03	<1	0.15	<10	0.84	3967	<2	0.01	2	331	2	0.14	<5	3	1015	<5	<0.01	<10	25	9	<10	31	2
83848	2.1	0.73	107	49	<0.5	6	4.07	3	27	9	89	5.95	<1	0.32	<10	0.40	1144	8	0.01	5	1430	36	>5.00	7	3	187	<5	<0.01	<10	23	21	<10	68	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2415RJ

Date : Jul-18-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 6

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
83849	2.5	2.62	78	146	<0.5	6	3.71	2	31	11	123	5.84	<1	0.21	<10	2.04	2352	<2	0.01	7	1265	13	0.76	<5	7	168	<5	<0.01	<10	35	84	<10	104	3
83850	3.6	2.97	76	122	<0.5	<5	4.88	2	22	6	254	5.77	<1	0.30	<10	2.17	2914	<2	0.01	5	1233	6	0.65	5	5	221	<5	0.01	<10	38	78	<10	94	4
83851	1.1	2.56	48	129	<0.5	<5	4.54	2	24	6	78	5.94	<1	0.32	<10	1.35	2285	<2	0.02	6	1405	4	0.96	<5	6	149	<5	0.04	<10	21	86	<10	78	4
83852	1.7	2.20	67	148	<0.5	5	6.53	2	25	9	62	4.85	<1	0.25	<10	1.05	2751	<2	0.02	7	1200	16	1.02	<5	5	209	<5	0.03	<10	40	83	<10	81	3
83853	3.8	1.68	81	159	<0.5	<5	4.69	3	13	4	48	4.11	<1	0.33	<10	0.82	2230	5	0.01	1	1210	173	1.04	<5	2	147	<5	0.03	<10	15	47	<10	220	3
83854	2.4	1.95	126	133	<0.5	5	3.98	3	21	6	39	5.80	<1	0.33	<10	1.00	2167	<2	0.01	2	1284	58	2.39	5	3	138	<5	0.06	<10	21	52	<10	167	4
83855	2.0	1.50	128	140	<0.5	5	5.93	3	13	5	31	4.10	<1	0.33	<10	0.71	2850	<2	0.01	2	1140	125	1.65	<5	2	178		0.03	<10	22	35	<10	185	3
83856	1.0	1.58	112	164	<0.5	<5	5.70	1	14	4	24	3.94	<1	0.35	<10	0.75	2111	2	0.02	1	1219	32	1.33	<5	2	165		0.05	<10	22	33	<10	38	3
83857	1.1	1.41	80	142	<0.5	<5	7.79	1	11	6	28	3.33	<1	0.30	<10	0.67	2564	<2	0.02	1	1110	49	0.81	<5	2	199		0.05	<10	26	30	<10	55	2
83858	1.1	1.89	78	142	<0.5	<5	4.85	1	16	3	39	4.88	<1	0.31	<10	0.99	2273	<2	0.02	2	1230	28	1.34	<5	2	156		0.06	<10	28	46	<10	55	3
83859	3.5	1.65	62	133	<0.5	<5	5.81	3	13	5	60	4.05	<1	0.29	<10	0.85	2383	<2	0.02	1	1145	92	0.97	<5	2	173		0.05	<10	24	42	<10	250	2
83860	6.7	1.89	73	126	<0.5	<5	5.17	3	14	4	30	4.58	<1	0.29	<10	1.00	2358	<2	0.02	2	1147	264	1.01	5	3	138		0.03	<10	22	49	<10	323	3
83861	1.6	1.38	112	106	<0.5	<5	5.07	1	11	16	15	3.64	<1	0.24	<10	0.75	2198	<2	0.02	2	914	18	1.14	6	2	197		0.05	<10	23	39	<10	47	2
83862	1.4	2.16	118	134	<0.5	<5	4.60	2	16	5	30	5.31	<1	0.31	<10	1.29	3050	<2	0.02	1	1326	28	1.52	<5	3	123		0.05	<10	26	72	<10	78	4
83863	1.5	2.56	180	176	<0.5	<5	5.42	3	19	7	43	6.91	<1	0.40	11	1.52	3267	<2	0.03	2	1857	26	2.52	5	4	186		0.05	<10	23	86	<10	103	5
83864	2.0	1.90	116	152	<0.5	<5	4.34	2	18	4	35	4.78	<1	0.24	<10	1.14	2298	<2	0.03	3	1137	19	1.55	<5	3	150		0.04	<10	35	63	<10	63	3
83865	1.4	1.88	80	145	<0.5	5	4.22	1	16	5	35	4.64	<1	0.34	<10	0.99	2263	<2	0.02	2	1279	13	1.20	<5	3	141		0.06	<10	23	58	<10	56	3
83866	1.0	1.71	83	139	<0.5	<5	4.00	2	13	5	32	4.28	<1	0.33	<10	0.90	2314	<2	0.02	2	1280	14	1.06	<5	3	164		0.01	<10	24	58	<10	98	3
83867	6.1	1.70	118	122	<0.5	<5	6.17	2	14	6	34	4.40	<1	0.32	<10	0.93	2686	<2	0.01	1	1231	26	1.46	6	3	164		0.01	<10	23	51	<10	77	3
83868	4.5	1.73	80	122	<0.5	5	3.17	3	13	6	39	4.40	<1	0.29	<10	0.99	1969	<2	0.02	1	1228	103	1.17	<5	2	102		<0.01	<10	22	47	<10	298	2
83869	13.1	1.83	49	135	<0.5	6	3.31	2	14	6	40	4.57	<1	0.33	<10	1.11	2334	<2	0.02	1	1303	93	0.94	6	3	135		<0.01	<10	27	50	<10	229	3
83870	10.7	0.68	56	167	<0.5	<5	3.63	1	13	15	28	3.56	<1	0.34	<10	0.80	2133	<2	0.02	1	1208	33	0.76	10	3	240		<0.01	<10	23	18	<10	46	2
83871	8.0	2.08	54	124	<0.5	<5	2.52	2	15	8	45	4.94	<1	0.34	<10	1.23	2378	<2	0.01	2	1299	207	0.91	<5	3	96		0.01	<10	31	55	<10	191	3
83872	10.7	1.78	190	133	<0.5	7	2.38	3	14	9	49	4.70	<1	0.39	<10	0.85	2002	<2	0.01	1	1215	133	1.58	6	2	69		0.01	<10	25	38	<10	289	3
83873	20.1	0.77	272	56	<0.5	8	1.64	18	12	23	170	4.46	<1	0.34	<10	0.23	1013	<2	0.01	1	951	1862	3.96	7	1	61		<0.01	<10	25	18	<10	2364	3
83874	12.3	1.12	259	75	<0.5	9	2.34	6	13	13	75	4.63	<1	0.36	<10	0.48	1478	2	0.01	2	1129	547	3.25	8	1	104		0.01	<10	28	27	<10	694	3
WDR08-02	10.5	0.93	16	219	<0.5	8	0.21	1	6	24	9	3.23	<1	0.28	22	0.20	81	3	0.03	4	1586	66	0.79	<5	3	<1		<0.01	14	<10	34	<10	116	5
WDR08-03	1.4	1.33	<5	138	<0.5	<5	0.07	1	7	13	15	4.11	1	0.16	<10	0.76	446	<2	0.03	1	421	17	1.79	<5	2	4		0.12	<10	16	32	<10	162	5
SP08-01	>200.0	0.14	34	24	<0.5	7	0.01	158	5	56	20	4.25	5	0.10	<10	0.02	46	5	0.03	1	98	8558	>5.00	154	<1	17		<0.01	<10	18	4	<10	>10000	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 35 Years

Assay Certificate

8V-2469-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment7**
Attn: **Sue Deane**

Jul-21-08

We hereby certify the following assay of 24 core samples submitted Jul-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
83875	0.37	0.32	6.0
83876	0.46		4.3
83877	0.10		1.0
83878	0.17		1.8
83879	0.18		1.8
83880	0.09		0.6
83881	0.11		0.3
83882	0.02		0.4
83883	0.02		0.3
83884	0.02	0.03	0.5
83885	0.01		0.3
83886	0.01		0.5
83887	0.01		0.4
83888	0.01		0.3
83889	0.01		0.1
83890	0.01		0.2
83891	0.02		0.3
83892	0.02		0.2
83893	0.04		0.5
83894	0.05	0.05	0.9
83895	0.07		1.1
83896	0.16		1.4
83897	0.06		1.0
83898	0.31		1.9
*0218	0.89		
*BLANK	<0.01		

Certified by _____

*Quality Assaying for over 35 Years***Assay Certificate****8V-2469-RA2**Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment7**
Attn: **Sue Deane**

Jul-21-08

We hereby certify the following assay of 24 core samples
submitted Jul-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
83899	0.37	0.32	3.0
83900	0.88		5.4
83901	0.52		4.0
83902	0.70		5.5
83903	0.47		5.8
83904	0.34		4.8
83905	0.87		4.6
83906	0.29		3.5
83907	0.35		3.4
83908	0.34	0.32	4.1
83909	0.41		3.0
83910	0.29		3.0
83911	0.55		3.4
83912	0.29		2.5
83913	0.27		4.6
83914	0.26		2.4
83915	0.10		0.7
83916	0.08		1.0
83917	0.12		1.5
83918	0.16	0.16	1.1
83919	0.21		1.1
83920	0.10		1.0
83921	2.00		3.4
83922	0.15		1.1
*0218	0.87		
*BLANK	<0.01		

Certified by _____

*Quality Assaying for over 35 Years***Assay Certificate****8V-2469-RA3**Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment7**
Attn: **Sue Deane**

Jul-21-08

We hereby certify the following assay of 24 core samples
submitted Jul-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
83923	0.30	0.30	4.0	
83924	0.12		0.6	
83925	0.04		0.7	
83926	0.08		0.8	
83927	0.07		0.8	
83927A	1.28		>200	234.1
83928	0.16		1.4	
83929	0.10		0.5	
83930	0.19		0.7	
83931	0.22	0.27	0.9	
83932	0.12		0.8	
83933	0.06		1.0	
83934	0.15		1.7	
83935	0.07		2.1	
83936	0.07		1.1	
83937	<0.01		0.2	
83938	0.09		1.7	
83939	0.08		2.1	
83940	0.06		0.7	
83941	0.04	0.06	1.2	
83942	0.06		0.8	
83943	0.02		0.8	
83944	0.10		1.3	
83945	0.08		1.2	
*0218	0.88			
*CCu-1c				129.2
*BLANK	<0.01			<0.1

Certified by _____

*Quality Assaying for over 35 Years***Assay Certificate****8V-2469-RA4**Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment7**
Attn: **Sue Deane**

Jul-21-08

We hereby certify the following assay of 24 core & rock samples
submitted Jul-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
83946	0.52	0.51	14.7	
83947	0.07		0.4	
139001	0.10		12.7	
139002	0.51		>200	624.0
139003	0.45		14.8	
139004	0.20		8.6	
139005	0.11		3.5	
139006	0.38		143.8	
139007	0.17		9.1	
139008	0.39	0.38	26.9	
139009	8.82		12.1	
139010	10.31		10.0	
139011	0.14		1.6	
139012	0.14		2.1	
139013	3.51		7.3	
139014	0.10		3.6	
139015	0.12		4.2	
139016	0.12		3.9	
139017	0.19		3.5	
139018	0.79	0.70	>200	834.0
139019	0.97		>200	953.0
139020	1.56		14.0	
139021	0.60		17.9	
139022	0.41		17.2	
*0218	0.87			
*CCu-1c				130.0
*BLANK	<0.01		<0.1	

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 35 Years

Assay Certificate

8V-2469-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment7**
Attn: **Sue Deane**

Jul-21-08

We *hereby certify* the following assay of 2 rock samples
submitted Jul-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
139023	0.59	0.66	40.5
*0218	0.91		
*BLANK	<0.01		

Certified by _____



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2469RJ

Date : Jul-21-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/shipment7

Attention : Sue Deane

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
83875	6.0	1.43	305	44	<0.5	8	2.05	3	15	17	31	6.17	<1	0.38	<10	0.78	1767	<2	0.01	3	0.109	90	4.78	15	2	79	<5	<0.01	<10	33	37	<10	201	4
83876	4.3	0.68	179	110	<0.5	<5	0.73	4	9	58	54	2.81	<1	0.31	<10	0.25	595	7	0.01	3	0.073	376	1.94	7	1	26	<5	<0.01	<10	12	18	<10	514	2
83877	1.0	1.68	104	84	<0.5	<5	2.00	2	15	13	6	5.25	<1	0.25	<10	1.27	2191	9	0.01	2	0.126	46	2.72	<5	3	66	<5	<0.01	<10	23	70	<10	143	3
83878	1.8	1.12	164	67	<0.5	<5	1.68	3	14	30	3	5.01	<1	0.22	<10	0.96	1836	7	0.01	3	0.106	163	3.29	<5	2	78	<5	0.01	<10	23	55	<10	244	3
83879	1.8	0.57	120	82	<0.5	<5	10.05	2	6	24	6	2.50	<1	0.17	<10	0.44	2830	3	0.01	2	0.045	81	1.28	<5	2	215	<5	<0.01	<10	20	18	<10	145	1
83880	0.6	2.37	21	228	<0.5	<5	5.73	1	15	10	42	4.31	<1	0.66	<10	0.95	2107	<2	0.02	2	0.112	22	0.61	5	5	156	<5	0.01	<10	20	65	<10	83	3
83881	0.3	2.23	20	181	<0.5	<5	6.28	1	15	9	29	4.02	<1	0.46	<10	1.10	2158	<2	0.05	2	0.112	14	0.44	<5	5	131	<5	0.07	<10	21	72	<10	77	3
83882	0.4	1.81	46	102	<0.5	<5	3.60	1	13	15	18	4.02	<1	0.32	<10	1.03	1857	<2	0.03	2	0.116	8	0.65	<5	4	125	<5	0.02	<10	18	54	<10	59	3
83883	0.3	2.28	25	104	<0.5	<5	2.88	1	16	7	35	5.11	<1	0.27	<10	1.33	2023	<2	0.03	2	0.127	5	0.53	<5	4	118	<5	0.03	<10	21	75	<10	81	3
83884	0.5	2.83	12	96	<0.5	<5	2.85	2	20	8	73	6.20	<1	0.27	<10	1.74	2304	<2	0.02	3	0.139	2	0.41	5	4	128	<5	0.01	<10	27	81	<10	111	4
83885	0.3	2.30	16	106	<0.5	<5	3.28	1	18	7	61	5.17	<1	0.29	<10	1.30	1983	<2	0.02	3	0.126	4	0.52	<5	4	135	<5	<0.01	<10	21	61	<10	84	3
83886	0.5	1.77	18	124	<0.5	<5	4.22	1	14	13	51	4.22	<1	0.28	<10	1.08	2100	<2	0.03	2	0.117	6	0.98	6	3	153	<5	0.01	<10	22	49	<10	65	3
83887	0.4	1.83	9	136	<0.5	<5	4.41	1	15	5	41	3.96	<1	0.33	<10	1.00	1801	<2	0.01	2	0.128	34	0.38	<5	3	165	<5	0.08	<10	16	42	<10	93	3
83888	0.3	1.62	11	232	<0.5	<5	4.50	1	14	11	41	3.90	<1	0.33	<10	0.84	1705	<2	0.02	2	0.120	6	0.68	<5	3	192	<5	0.04	<10	14	40	<10	59	3
83889	<0.2	1.62	<5	385	<0.5	<5	2.99	1	14	7	24	3.96	<1	0.33	<10	0.97	1534	<2	0.02	2	0.126	2	0.41	<5	3	207	<5	0.02	<10	14	37	<10	59	4
83890	0.2	0.64	<5	158	<0.5	<5	3.94	1	10	46	9	3.13	<1	0.37	<10	0.74	1710	<2	0.02	2	0.103	<2	0.37	<5	3	307	<5	<0.01	<10	18	15	<10	31	2
83891	0.3	1.57	49	105	<0.5	<5	5.47	1	14	7	23	4.07	<1	0.33	<10	0.85	1947	<2	0.02	2	0.116	6	1.29	5	4	171	<5	0.02	<10	19	47	<10	48	3
83892	0.2	1.47	33	89	<0.5	<5	8.42	1	10	15	19	3.24	<1	0.34	<10	0.80	2141	<2	0.02	2	0.116	19	0.67	<5	3	255	<5	0.03	<10	20	39	<10	44	3
83893	0.5	1.61	67	100	<0.5	<5	6.87	1	12	8	27	3.49	<1	0.35	<10	0.88	2236	<2	0.02	2	0.122	21	1.11	<5	3	218	<5	0.05	<10	20	43	<10	59	3
83894	0.9	0.87	121	100	<0.5	5	4.49	1	17	31	40	4.07	<1	0.35	<10	0.71	1768	<2	0.01	2	0.118	16	2.18	5	2	297	<5	<0.01	<10	24	22	<10	42	2
83895	1.1	1.52	73	123	<0.5	6	4.77	2	22	8	81	5.16	<1	0.47	<10	0.95	1913	<2	0.01	3	0.114	8	1.93	<5	3	189	<5	<0.01	<10	24	34	<10	47	3
83896	1.4	1.57	88	116	<0.5	<5	3.89	4	15	19	25	4.05	<1	0.39	<10	0.74	1926	<2	0.01	2	0.116	40	1.30	<5	2	284	<5	<0.01	<10	24	34	<10	402	2
83897	1.0	1.43	63	101	<0.5	<5	4.88	1	13	15	27	3.78	<1	0.37	<10	0.60	1997	<2	0.01	2	0.108	13	1.34	<5	2	198	<5	<0.01	<10	25	33	<10	79	2
83898	1.9	1.32	77	122	<0.5	<5	1.43	1	15	20	36	3.50	<1	0.43	<10	0.51	1051	<2	0.01	2	0.131	11	1.52	<5	2	47	<5	0.01	<10	12	27	<10	59	2
83899	3.0	0.43	148	125	<0.5	<5	0.39	2	7	78	71	2.53	<1	0.21	<10	0.20	604	21	0.01	4	0.060	54	1.33	7	1	35	<5	<0.01	<10	<10	11	<10	208	2
83900	5.4	1.21	372	96	<0.5	<5	0.22	3	11	76	221	4.57	<1	0.16	<10	0.68	1353	22	0.01	4	0.064	28	1.84	13	4	9	<5	0.01	<10	14	75	<10	197	3
83901	4.0	1.63	91	109	<0.5	<5	0.28	3	14	47	191	4.63	<1	0.17	<10	1.01	1838	12	0.01	4	0.080	20	1.12	6	4	11	<5	0.01	<10	16	106	<10	257	3
83902	5.5	1.88	91	118	<0.5	<5	0.21	3	14	55	330	5.18	<1	0.18	<10	1.29	2036	8	0.01	5	0.085	12	1.21	8	5	6	<5	<0.01	<10	17	130	<10	274	3
83903	5.8	2.04	75	121	<0.5	5	0.35	3	18	35	392	5.21	<1	0.30	<10	1.24	2005	10	0.01	5	0.107	12	1.20	7	5	14	<5	<0.01	<10	19	102	<10	291	3
83904	4.8	1.03	191	109	<0.5	5	0.27	3	15	86	279	4.70	<1	0.24	<10	0.57	1003	11	0.01	6	0.079	146	2.67	8	3	15	<5	<0.01	<10	12	65	<10	258	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2469RJ

Date : Jul-21-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/shipment7

Attention : Sue Deane

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
83905	4.6	1.24	146	134	<0.5	6	0.41	3	16	48	228	4.89	<1	0.29	<10	0.63	1532	15	0.01	4	0.112	18	2.16	9	4	19	<5	<0.01	<10	11	79	<10	229	3
83906	3.5	1.25	143	135	<0.5	5	0.42	3	14	95	173	4.34	<1	0.27	<10	0.65	1525	17	0.01	5	0.093	26	1.47	6	3	23	<5	<0.01	<10	14	64	<10	207	3
83907	3.4	0.87	669	128	<0.5	5	0.87	3	12	58	148	4.42	<1	0.27	<10	0.74	2097	12	0.01	4	0.086	33	1.20	19	3	64	<5	<0.01	<10	16	43	<10	259	3
83908	4.1	0.79	190	121	<0.5	<5	0.54	5	10	103	113	4.00	<1	0.23	<10	0.54	1214	11	0.01	4	0.080	725	1.56	9	3	34	<5	<0.01	<10	15	30	<10	476	3
83909	3.0	0.44	923	145	<0.5	<5	0.74	3	10	78	117	2.73	<1	0.25	<10	0.33	948	6	0.01	4	0.074	126	1.25	19	3	42	<5	<0.01	<10	<10	21	<10	285	2
83910	3.0	0.36	438	331	<0.5	<5	0.55	2	10	160	98	2.53	<1	0.25	<10	0.19	2921	12	0.01	5	0.062	61	0.95	15	2	36	<5	<0.01	<10	17	12	<10	211	2
83911	3.4	0.83	124	120	<0.5	5	1.13	3	15	57	163	4.26	<1	0.29	<10	0.68	1560	18	0.01	4	0.105	21	1.56	7	4	67	<5	<0.01	<10	14	48	<10	242	3
83912	2.5	0.46	160	106	<0.5	<5	0.78	2	9	122	101	3.24	<1	0.22	<10	0.47	1087	18	0.01	5	0.073	45	1.31	8	3	61	<5	<0.01	<10	10	33	<10	236	2
83913	4.6	0.25	242	84	<0.5	<5	0.31	5	9	90	101	3.31	<1	0.18	<10	0.20	468	9	0.01	5	0.048	565	2.32	10	2	23	<5	<0.01	<10	11	12	<10	583	2
83914	2.4	0.27	260	85	<0.5	6	0.64	8	8	144	40	3.93	<1	0.21	<10	0.16	613	8	0.01	5	0.061	198	3.06	8	2	48	<5	<0.01	<10	12	9	<10	902	3
83915	0.7	0.69	37	83	<0.5	<5	1.74	2	8	88	53	3.47	<1	0.23	<10	0.66	1271	8	0.02	4	0.082	18	0.48	5	4	105	<5	<0.01	<10	10	22	<10	181	2
83916	1.0	0.86	49	78	<0.5	<5	0.70	2	8	102	43	3.16	<1	0.20	<10	0.62	832	6	0.01	4	0.084	15	0.67	8	3	34	<5	<0.01	<10	<10	28	<10	153	2
83917	1.5	0.48	95	120	<0.5	<5	0.41	2	9	94	43	3.21	<1	0.26	<10	0.34	791	6	0.01	4	0.086	18	1.24	9	2	29	<5	<0.01	<10	<10	13	<10	144	3
83918	1.1	0.44	84	146	<0.5	<5	1.48	2	11	132	64	3.67	<1	0.33	<10	0.43	1172	10	0.01	5	0.096	12	0.79	8	3	97	<5	<0.01	<10	12	12	<10	136	3
83919	1.1	0.69	85	100	<0.5	<5	2.91	2	9	64	53	3.96	<1	0.25	<10	0.78	1658	5	0.02	3	0.094	14	0.48	6	4	190	<5	<0.01	<10	16	24	<10	127	2
83920	1.0	0.56	49	401	<0.5	5	2.50	2	12	105	85	3.69	<1	0.34	<10	0.54	1505	6	0.02	4	0.099	24	0.31	6	3	213	<5	<0.01	<10	12	16	<10	135	2
83921	3.4	0.33	161	95	<0.5	<5	2.44	27	9	96	101	3.54	<1	0.30	<10	0.48	1097	5	0.01	4	0.078	440	1.76	7	3	216	<5	<0.01	<10	12	10	<10	2967	2
83922	1.1	0.56	33	148	<0.5	<5	2.89	2	13	67	102	4.49	<1	0.35	<10	0.89	1700	12	0.01	4	0.114	21	0.77	6	3	255	<5	<0.01	<10	13	21	<10	160	3
83923	4.0	0.41	95	145	<0.5	5	2.02	5	9	98	120	3.87	<1	0.25	<10	0.63	1392	7	0.02	5	0.075	46	1.26	8	3	162	<5	<0.01	<10	18	21	<10	528	2
83924	0.6	0.75	25	151	<0.5	5	2.09	2	10	128	44	3.74	<1	0.24	<10	0.66	1213	8	0.02	6	0.076	8	0.55	5	4	137	<5	<0.01	<10	17	35	<10	148	2
83925	0.7	0.48	43	294	<0.5	<5	2.71	2	8	74	39	3.48	<1	0.30	<10	0.66	1444	6	0.02	3	0.084	12	0.40	<5	4	211	<5	<0.01	<10	17	16	<10	126	2
83926	0.8	0.36	17	336	<0.5	<5	2.94	4	5	147	32	2.98	<1	0.25	<10	0.68	1356	5	0.02	5	0.073	66	0.29	6	3	254	<5	<0.01	<10	17	12	<10	383	2
83927	0.8	1.09	16	79	<0.5	5	2.70	2	9	67	52	3.77	<1	0.18	<10	0.80	1352	4	0.03	4	0.083	5	0.37	<5	5	143	<5	<0.01	<10	16	49	<10	130	2
83927A	>200.0	0.87	1838	89	<0.5	62	4.16	2	57	23	2311	2.95	1	0.09	<10	0.23	853	126	0.06	23	0.081	367	0.63	436	2	126	<5	0.04	12	22	20	15	294	8
83928	1.4	1.11	670	112	<0.5	5	1.88	2	9	106	52	3.74	<1	0.20	<10	0.58	1276	17	0.02	4	0.081	17	0.67	12	3	61	5	<0.01	<10	20	50	<10	209	3
83929	0.5	1.24	26	86	<0.5	5	2.16	1	9	82	35	3.54	<1	0.21	<10	0.66	1025	4	0.02	4	0.082	4	0.42	<5	3	87	6	<0.01	<10	19	49	<10	124	2
83930	0.7	1.27	43	69	<0.5	5	1.84	1	9	118	49	3.60	<1	0.18	<10	0.66	918	6	0.02	4	0.075	7	0.65	5	3	52	5	<0.01	<10	19	46	<10	129	2
83931	0.9	1.10	54	67	<0.5	<5	1.33	1	9	96	41	3.25	<1	0.18	<10	0.53	802	3	0.02	4	0.068	9	0.58	6	2	50	7	<0.01	13	19	37	<10	110	2
83932	0.8	1.43	17	76	<0.5	5	1.49	1	10	87	69	3.75	<1	0.17	<10	0.79	876	4	0.02	4	0.087	4	0.35	<5	3	50	8	<0.01	11	19	56	<10	127	2
83933	1.0	1.00	37	59	<0.5	5	0.80	1	7	118	25	3.48	<1	0.18	<10	0.55	589	4	0.02	4	0.058	6	1.47	7	2	28	8	<0.01	14	20	32	<10	79	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2469RJ

Date : Jul-21-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/shipment7

Multi-Element ICP-AES Analysis

Attention : Sue Deane

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
83934	1.7	1.18	70	77	<0.5	5	0.94	2	9	78	41	3.41	<1	0.21	<10	0.63	771	7	0.01	3	0.069	46	0.97	7	2	31	8	<0.01	17	21	36	<10	153	2
83935	2.1	1.49	58	152	<0.5	6	1.58	2	10	42	62	4.21	<1	0.28	<10	0.82	974	3	0.02	3	0.089	29	1.21	7	3	65	9	<0.01	<10	24	45	<10	124	3
83936	1.1	1.39	31	74	<0.5	<5	1.99	1	10	52	51	3.67	<1	0.24	<10	0.80	891	5	0.03	3	0.084	53	0.76	<5	4	51	7	0.01	10	22	55	<10	94	2
83937	0.2	0.77	<5	70	<0.5	<5	2.16	<1	8	34	11	2.01	<1	0.35	14	0.56	657	<2	0.03	4	0.071	2	0.49	<5	3	110	8	<0.01	16	<10	17	<10	30	6
83938	1.7	0.89	53	62	<0.5	5	0.88	1	9	77	50	4.16	<1	0.22	<10	0.67	794	6	0.02	3	0.068	17	1.75	5	3	38	7	<0.01	<10	23	28	<10	99	2
83939	2.1	0.28	75	43	<0.5	7	2.46	2	7	69	25	5.15	<1	0.21	<10	0.63	1049	<2	0.01	3	0.059	57	3.77	8	2	144	7	<0.01	<10	31	8	<10	105	3
83940	0.7	1.06	54	57	<0.5	5	2.05	2	9	70	31	3.79	<1	0.19	<10	0.65	1152	3	0.01	2	0.068	16	1.47	5	3	46	<5	<0.01	<10	20	37	<10	143	2
83941	1.2	1.07	36	57	<0.5	6	3.05	1	7	86	32	3.73	<1	0.16	<10	0.61	1339	3	0.02	3	0.060	9	1.79	7	3	72	12	<0.01	31	33	36	<10	107	2
83942	0.8	1.24	35	77	<0.5	5	2.05	1	7	108	15	3.16	<1	0.24	<10	0.67	1178	4	0.02	4	0.072	4	0.74	5	3	49	13	<0.01	32	26	33	<10	97	2
83943	0.8	1.09	25	97	<0.5	<5	1.44	1	8	54	15	3.35	<1	0.29	<10	0.78	1146	<2	0.02	2	0.093	4	0.54	<5	3	28	13	<0.01	30	22	32	<10	90	2
83944	1.3	0.33	102	121	<0.5	<5	3.08	1	7	128	21	2.86	<1	0.25	<10	0.41	1285	8	0.01	4	0.056	23	1.47	6	2	101	10	<0.01	32	28	8	<10	76	2
83945	1.2	0.77	110	145	<0.5	<5	2.60	1	6	41	8	2.79	<1	0.35	<10	0.45	1104	<2	0.01	2	0.077	12	1.35	<5	1	75	11	<0.01	30	26	18	<10	52	4
83946	14.7	1.02	175	107	<0.5	5	1.89	5	8	76	29	4.08	<1	0.35	<10	0.53	1105	2	0.01	4	0.084	700	2.10	5	2	61	<5	<0.01	<10	16	27	<10	620	4
83947	0.4	1.14	46	156	<0.5	<5	2.96	1	8	106	19	3.83	<1	0.27	<10	0.74	1443	3	0.01	5	0.075	10	1.03	<5	3	139	<5	<0.01	<10	15	30	<10	101	3
139001	12.7	0.68	284	139	<0.5	5	0.39	1	7	90	33	3.24	<1	0.23	<10	0.24	329	3	0.01	5	0.077	105	1.52	19	1	16	<5	<0.01	<10	<10	17	<10	115	2
139002	>200.0	0.27	445	83	<0.5	8	0.22	26	5	121	72	4.50	2	0.24	<10	0.02	112	2	0.01	5	0.028	3212	3.80	74	<1	17	<5	<0.01	<10	<10	10	<10	3463	2
139003	14.8	0.28	321	64	<0.5	10	0.34	52	6	151	56	5.78	2	0.18	<10	0.08	239	2	0.02	6	0.035	3702	5.44	16	<1	27	<5	<0.01	<10	17	11	<10	6710	3
139004	8.6	0.65	193	130	<0.5	7	0.11	3	5	127	8	4.09	<1	0.21	<10	0.30	510	<2	0.02	5	0.053	241	2.22	15	1	6	<5	<0.01	<10	<10	26	<10	308	2
139005	3.5	1.05	168	121	<0.5	<5	0.15	1	6	112	<1	3.92	<1	0.17	<10	0.66	1061	4	0.01	5	0.069	63	1.56	10	2	<1	<5	<0.01	<10	10	56	<10	92	3
139006	143.8	0.76	223	127	<0.5	7	0.13	6	6	98	56	4.20	<1	0.23	<10	0.34	753	2	0.01	5	0.066	328	2.30	29	1	8	<5	<0.01	<10	11	27	<10	868	3
139007	9.1	1.44	149	153	<0.5	8	0.40	5	15	84	121	5.50	<1	0.32	<10	0.69	1702	4	0.01	6	0.087	359	2.35	12	2	15	<5	0.01	<10	20	41	<10	405	3
139008	26.9	1.55	276	144	<0.5	8	0.22	17	14	48	132	5.90	2	0.33	<10	0.76	1710	9	0.01	5	0.103	2582	2.41	20	2	24	<5	<0.01	<10	21	47	<10	1701	3
139009	12.1	1.05	244	98	<0.5	7	0.16	5	8	60	149	5.15	<1	0.19	<10	0.53	881	22	0.02	5	0.091	616	2.14	7	2	6	<5	<0.01	<10	12	33	<10	568	3
139010	10.0	1.27	93	95	<0.5	7	0.21	2	10	42	192	5.05	<1	0.23	12	0.64	994	40	0.03	4	0.102	357	1.39	6	2	7	<5	<0.01	<10	<10	34	<10	221	3
139011	1.6	1.10	213	101	<0.5	7	0.20	1	8	34	57	4.38	<1	0.25	<10	0.51	685	16	0.02	3	0.104	33	1.05	5	2	5	<5	<0.01	<10	<10	31	<10	85	2
139012	2.1	1.15	104	168	<0.5	5	0.18	1	7	38	81	3.99	<1	0.23	<10	0.53	817	15	0.01	3	0.098	41	0.52	<5	2	7	<5	<0.01	<10	<10	32	<10	108	2
139013	7.3	1.29	203	135	<0.5	6	0.17	1	6	41	113	4.60	<1	0.24	<10	0.60	883	9	0.02	3	0.099	107	0.88	6	2	10	<5	<0.01	<10	10	35	<10	65	2
139014	3.6	0.88	63	185	<0.5	7	0.10	1	6	33	125	4.45	<1	0.26	<10	0.35	636	8	0.02	3	0.109	17	0.66	5	2	10	<5	<0.01	<10	<10	26	<10	75	2
139015	4.2	1.24	112	137	<0.5	5	0.16	1	6	62	87	3.98	<1	0.22	<10	0.60	977	38	0.02	4	0.089	110	0.67	<5	2	5	<5	<0.01	<10	<10	43	<10	95	2
139016	3.9	1.31	89	91	<0.5	6	0.18	1	8	41	86	3.90	<1	0.19	<10	0.66	1044	8	0.02	4	0.086	37	0.76	<5	2	5	<5	<0.01	<10	<10	38	<10	98	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2469RJ

Date : Jul-21-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/shipment7

Attention : Sue Deane

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139017	3.5	1.38	116	152	<0.5	5	0.18	1	6	59	57	4.46	<1	0.24	<10	0.63	1128	10	0.02	3	0.097	34	0.76	7	2	6	<5	<0.01	<10	12	46	<10	95	2
139018	>200.0	0.79	464	82	<0.5	8	0.13	16	4	61	71	4.93	<1	0.21	<10	0.35	583	16	0.02	3	0.072	1585	2.93	72	1	6	<5	<0.01	<10	13	29	<10	2699	3
139019	>200.0	0.44	998	27	<0.5	14	0.08	27	5	61	186	8.08	1	0.20	<10	0.16	374	27	0.01	3	0.046	2274	8.08	109	1	3	<5	<0.01	<10	23	20	<10	4369	4
139020	14.0	0.70	301	148	<0.5	5	0.15	1	6	77	79	3.33	<1	0.21	<10	0.30	725	19	0.01	3	0.061	183	1.02	8	1	4	<5	<0.01	<10	<10	28	<10	144	2
139021	17.9	0.66	454	153	<0.5	6	0.09	1	5	97	171	4.28	<1	0.21	<10	0.23	1023	10	0.01	4	0.051	72	1.62	12	2	4	<5	<0.01	<10	<10	20	<10	114	2
139022	17.2	0.97	391	166	<0.5	6	0.14	2	9	105	237	4.35	<1	0.20	<10	0.48	1326	33	0.01	5	0.062	364	0.98	15	3	5	<5	<0.01	<10	<10	40	<10	389	3
139023	40.5	0.26	924	78	<0.5	10	0.03	5	6	87	95	5.68	<1	0.14	<10	0.09	442	8	<0.01	3	0.033	696	2.52	31	1	<1	<5	<0.01	<10	15	20	<10	698	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Signed: _____ 



Quality Assaying for over 35 Years

Assay Certificate

8V-2472-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment8**
Attn: **Sue Deane**

Jul-22-08

We hereby certify the following assay of 24 core samples submitted Jul-10-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
83948	0.06	0.06	1.2
83949	0.09		1.6
83950	0.09		1.1
83951	0.12		1.0
83952	0.16		3.7
83953	0.30		1.2
83954	0.21		1.3
83955	0.18		1.3
83955A	<0.01		<0.1
83956	0.27	0.21	1.3
83957	0.21		1.3
83958	0.23		1.4
83959	0.13		1.0
83960	0.15		0.9
83961	0.05		0.7
83962	0.10		1.4
83963	0.14		1.8
83964	0.23		1.7
83965	0.13		2.0
83966	0.03	0.03	2.0
83967	0.04		1.1
83968	0.13		1.4
83969	0.09		3.4
83970	0.12		2.4
*0218	0.90		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 35 Years

Assay Certificate

8V-2472-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment8**
Attn: **Sue Deane**

Jul-22-08

We *hereby certify* the following assay of 24 core samples submitted Jul-10-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
83971	0.16	0.13	1.7
83972	0.20		3.0
83973	0.14		2.3
83974	0.12		3.6
83975	0.12		3.2
83976	0.12		1.7
83977	0.10		3.4
83978	0.10		4.5
83979	0.18		1.7
83979A	0.01	<0.01	<0.1
83980	0.24		3.9
83981	0.15		2.6
83982	1.90		6.0
83983	0.24		3.1
83984	0.12		3.8
83985	0.17		3.8
83986	0.20		2.6
83987	0.12		3.3
83988	0.10		2.6
83989	0.19	0.19	3.7
83990	0.14		2.8
83991	0.05		1.6
83992	0.06		1.3
83993	0.14		2.8
*0218	0.93		
*BLANK	<0.01		

Certified by _____





Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 35 Years

Assay Certificate

8V-2472-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment8**
Attn: **Sue Deane**

Jul-22-08

We *hereby certify* the following assay of 24 core samples submitted Jul-10-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
83994	0.08	0.09	1.3	
83995	0.11		5.6	
83996	0.19		1.3	
83997	0.05		1.1	
83998	0.33		3.2	
83999	0.10		12.9	
84000	0.12		2.6	
84001	0.12		1.5	
84002	0.09		1.5	
84003	0.22	0.20	1.8	
84004	0.09		1.2	
84005	0.09		3.3	
84006	0.07		2.0	
84007	0.10		3.7	
84008	0.06		3.3	
84009	0.07		5.5	
84010	0.15		6.6	
84010A	1.33		>200	231.9
84011	0.07		1.1	
84012	0.02	0.03	0.4	
84013	0.02		0.9	
84014	0.03		0.5	
84015	<0.01		0.4	
84016	<0.01		<0.1	
*0218	0.95			
*CCu-1c				130.2
*BLANK	<0.01			<0.1

Certified by _____



Quality Assaying for over 35 Years

Assay Certificate

8V-2472-RA4

Company: **Ascot Resources Ltd**
Project: Dilworth/PO#shipment8
Attn: Sue Deane

Jul-22-08

We hereby certify the following assay of 24 core samples submitted Jul-10-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
84017	0.13	0.13	0.6	
84018	0.12		1.0	
84019	0.02		<0.1	
84020	0.01		<0.1	
84021	<0.01		<0.1	
84022	0.11		0.9	
84023	0.09		0.5	
84024	0.28		6.4	
84025	0.42		6.6	
84026	<0.01	<0.01	<0.1	
84027	1.36		>200	226.9
84028	0.62		7.0	
84029	0.62		4.8	
84030	0.63		4.2	
84031	0.43		4.0	
84032	0.33		3.3	
84033	0.50		4.7	
84034	0.32		6.2	
84035	0.23		3.6	
84036	0.29	0.28	3.3	
84037	0.35		3.4	
84038	0.37		2.1	
84039	0.89		5.1	
84040	0.71		8.4	
*0218	0.86			
*CCu-1c				130.2
*BLANK	<0.01			<0.1

Certified by _____

Quality Assaying for over 35 Years

Assay Certificate

8V-2472-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment8**
Attn: **Sue Deane**

Jul-22-08

We hereby certify the following assay of 24 core samples submitted Jul-10-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
84041	0.25	0.27	17.9	0.93
84042	0.15		8.6	
84042A	0.21		10.5	
84043	0.05		1.2	
84044	0.04		0.9	
84045	0.02		0.3	
84046	0.11		0.3	
84047	0.15		0.2	
84048	0.05		0.2	
84049	0.06	0.04	0.2	
84050	0.13		0.4	
84051	0.06		0.3	
84052	0.10		0.3	
84053	0.06		0.3	
84054	0.11		0.1	
84055	0.10		0.3	
84056	0.31		2.0	
84057	0.03		0.2	
84058	0.07		0.1	
84058A	<0.01	0.01	<0.1	
84059	0.06		0.1	
84060	0.02		0.6	
84061	0.09		0.3	
84062	0.11		0.3	
*0218	0.91			
*CCu-1c				3.93
*BLANK	<0.01			<0.01

Certified by _____



Quality Assaying for over 35 Years

Assay Certificate

8V-2472-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment8**
Attn: **Sue Deane**

Jul-22-08

We hereby certify the following assay of 24 core samples submitted Jul-10-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84063	0.37	0.41	1.5
84064	0.32		1.9
84065	0.10		0.4
84066	0.09		0.3
84067	0.05		<0.1
84068	0.11		0.5
84069	0.07		0.1
84070	0.10		0.6
84071	0.05		0.2
84072	0.11	0.11	0.5
84073	0.07		0.4
84074	0.04		0.4
84075	0.05		0.5
84076	0.32		3.6
84077	0.10		0.8
84078	0.10		3.3
84079	0.06		0.6
84080	0.07		1.5
84081	0.09		2.4
84082	0.10	0.12	2.6
84083	0.10		0.9
84084	0.05		0.2
84085	0.01		<0.1
84086	1.80		175.3
*0218	0.93		
*BLANK	<0.01		

Certified by _____



Quality Assaying for over 35 Years

Assay Certificate

8V-2472-RA7

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment8**
Attn: **Sue Deane**

Jul-22-08

We hereby certify the following assay of 24 core samples submitted Jul-10-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84087	0.05	0.06	0.3
84088	0.07		0.4
84089	0.07		0.2
84090	0.10		0.2
84091	0.05		0.5
84092	0.09		0.3
84093	0.16		0.9
84094	0.07		0.1
84095	0.21		0.3
84096	0.09	0.10	0.2
84097	0.11		0.1
84098	0.12		0.1
84099	0.18		0.4
84100	0.23		0.2
84101	0.25		0.2
84102	0.22		<0.1
84103	0.23		0.3
84104	0.11		<0.1
84105	0.08		<0.1
84106	0.15	0.18	<0.1
84107	0.04		0.1
84108	0.06		0.1
84109	0.04		<0.1
84110	0.05		1.1
*0218	0.78		
*BLANK	<0.01		

Certified by _____





Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 35 Years

Assay Certificate

8V-2472-RA8

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment8**
Attn: **Sue Deane**

Jul-22-08

We *hereby certify* the following assay of 3 core samples submitted Jul-10-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84111	0.08	0.09	3.6
84112	0.02		2.6
*0218	0.92		
*BLANK	<0.01		

Certified by _____



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2472RJ

Date : Jul-22-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/PO#shipment8

Attention : Sue Deane

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
83948	1.2	0.59	49	119	<0.5	<5	2.80	3	8	74	<1	3.47	<1	0.37	<10	0.70	1413	5	0.02	4	0.090	16	0.79	5	3	185	<5	<0.01	<10	14	12	<10	203	3
83949	1.6	0.72	46	135	<0.5	<5	2.52	2	7	134	<1	3.86	<1	0.35	<10	0.54	1419	6	0.02	5	0.083	17	0.59	6	4	113	<5	<0.01	<10	16	17	<10	123	3
83950	1.1	1.16	34	88	<0.5	<5	1.94	1	8	93	34	3.78	<1	0.26	<10	0.76	1196	3	0.02	4	0.081	7	0.82	5	4	67	<5	0.01	<10	15	35	<10	118	3
83951	1.0	1.50	36	107	<0.5	<5	1.98	3	8	105	24	3.87	<1	0.28	10	0.77	1331	6	0.03	4	0.090	23	0.55	5	3	62	<5	<0.01	<10	12	43	<10	368	3
83952	3.7	1.10	87	72	<0.5	<5	3.43	2	9	86	54	3.57	<1	0.28	<10	0.65	1555	9	0.01	5	0.084	19	1.59	5	2	97	<5	<0.01	<10	21	31	<10	228	3
83953	1.2	1.39	52	71	<0.5	<5	2.37	2	9	93	30	3.96	<1	0.25	<10	0.78	1316	11	0.02	6	0.078	6	1.11	<5	3	74	<5	<0.01	<10	17	52	<10	98	3
83954	1.3	1.24	83	69	<0.5	<5	3.21	1	11	89	95	4.11	<1	0.32	<10	0.80	1393	11	0.01	6	0.090	6	1.82	5	3	108	<5	<0.01	<10	17	39	<10	70	3
83955	1.3	0.72	107	63	<0.5	<5	4.35	2	11	88	58	3.93	<1	0.33	<10	0.74	1933	6	0.01	5	0.078	138	1.46	<5	3	299	<5	<0.01	<10	23	15	<10	87	2
83955A	<0.2	1.04	<5	237	<0.5	<5	0.54	<1	6	132	<1	2.10	<1	0.52	<10	0.61	568	<2	0.09	7	0.074	<2	<0.01	<5	2	58	5	0.13	<10	<10	38	<10	49	3
83956	1.3	1.19	52	196	<0.5	<5	2.55	4	9	112	45	3.38	<1	0.23	<10	0.74	1241	13	0.02	5	0.069	278	1.04	5	3	113	<5	0.01	<10	17	38	<10	330	3
83957	1.3	1.81	89	173	<0.5	<5	2.84	2	13	63	87	4.92	<1	0.30	<10	1.08	1484	15	0.02	6	0.097	8	1.59	5	4	93	<5	0.02	<10	20	61	<10	115	4
83958	1.4	1.87	24	211	<0.5	<5	3.19	3	13	81	51	4.49	<1	0.22	<10	1.12	1402	9	0.03	7	0.092	185	0.60	<5	4	104	<5	0.03	<10	20	70	<10	235	4
83959	1.0	1.51	21	91	<0.5	<5	5.23	4	10	43	17	4.04	<1	0.20	<10	0.88	1792	4	0.03	4	0.083	13	0.65	<5	3	133	<5	0.01	<10	19	61	<10	357	2
83960	0.9	1.78	23	108	<0.5	<5	3.17	2	12	51	26	4.61	<1	0.26	<10	1.06	1368	5	0.03	5	0.101	5	0.57	<5	4	91	<5	0.01	<10	20	71	<10	105	3
83961	0.7	1.40	14	129	<0.5	<5	2.63	1	10	42	22	3.86	<1	0.18	<10	0.77	1183	5	0.03	4	0.089	4	0.50	<5	4	79	<5	0.03	<10	15	64	<10	108	3
83962	1.4	0.44	26	321	<0.5	5	1.54	2	13	88	66	4.64	<1	0.31	<10	0.71	1321	7	0.02	5	0.101	9	0.61	5	3	73	<5	<0.01	<10	19	29	<10	105	2
83963	1.8	1.17	24	61	<0.5	<5	4.98	1	10	48	63	3.88	<1	0.23	<10	0.73	1654	8	0.03	4	0.084	7	0.66	<5	3	142	<5	<0.01	<10	18	49	<10	121	2
83964	1.7	1.42	43	72	<0.5	<5	4.96	2	12	62	141	4.50	<1	0.23	<10	0.76	1957	17	0.03	5	0.093	12	0.79	<5	4	138	<5	<0.01	<10	23	64	<10	181	3
83965	2.0	1.80	33	76	<0.5	<5	3.19	3	13	42	193	5.28	<1	0.22	<10	1.00	1628	5	0.04	5	0.102	47	1.05	<5	5	84	<5	0.01	<10	22	84	<10	203	3
83966	2.0	0.83	17	122	<0.5	<5	3.82	2	11	79	171	4.72	<1	0.29	<10	0.99	1840	11	0.03	5	0.097	8	0.60	6	4	143	<5	<0.01	<10	20	41	<10	137	3
83967	1.1	0.91	15	72	<0.5	<5	2.48	2	11	93	111	3.92	<1	0.24	<10	0.74	1377	7	0.03	6	0.094	7	0.51	5	4	81	<5	<0.01	<10	17	45	<10	144	2
83968	1.4	0.52	45	230	<0.5	<5	1.67	3	13	156	55	4.35	<1	0.33	<10	0.75	1359	7	0.03	8	0.103	107	1.09	8	4	79	<5	<0.01	<10	19	27	<10	250	3
83969	3.4	0.97	110	62	<0.5	<5	2.98	7	11	92	58	4.31	<1	0.31	<10	0.75	1797	3	0.02	6	0.086	845	1.67	7	3	58	<5	<0.01	<10	22	39	<10	776	2
83970	2.4	0.42	161	73	<0.5	<5	3.80	2	9	123	44	3.80	<1	0.31	<10	0.41	1910	7	0.01	6	0.078	55	2.31	8	3	71	<5	<0.01	<10	19	17	<10	199	2
83971	1.7	1.55	17	114	<0.5	<5	3.24	2	12	35	156	4.08	<1	0.24	<10	1.01	1630	4	0.02	4	0.104	8	0.37	<5	5	102	<5	0.05	<10	14	68	<10	165	3
83972	3.0	0.75	39	97	<0.5	<5	3.17	2	11	48	264	3.87	<1	0.27	<10	0.63	1703	8	0.01	4	0.095	13	1.12	<5	4	68	<5	<0.01	<10	17	33	<10	143	2
83973	2.3	1.13	123	162	<0.5	<5	5.16	3	12	33	172	4.32	<1	0.26	<10	0.77	2355	11	0.01	3	0.095	110	1.30	<5	3	127	<5	<0.01	<10	22	43	<10	222	3
83974	3.6	1.39	91	112	<0.5	<5	3.75	2	14	37	222	4.67	<1	0.24	<10	1.02	2173	18	0.01	3	0.108	19	1.35	<5	4	133	<5	<0.01	<10	21	66	<10	158	3
83975	3.2	0.30	120	44	<0.5	<5	4.00	2	11	70	129	3.78	<1	0.25	<10	0.74	2056	9	0.01	2	0.086	30	1.41	6	4	185	<5	<0.01	<10	22	15	<10	156	2
83976	1.7	0.93	78	157	<0.5	<5	3.65	2	16	40	89	5.00	<1	0.28	<10	0.74	1769	6	0.01	3	0.116	27	1.20	<5	4	113	<5	<0.01	<10	21	57	<10	148	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2472RJ

Date : Jul-22-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/PO#shipment8

Attention : Sue Deane

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
83977	3.4	0.59	99	90	<0.5	<5	2.60	9	15	65	157	5.21	<1	0.29	<10	0.85	1885	13	0.01	3	0.110	270	2.03	6	3	85	<5	<0.01	<10	22	30	<10	914	3
83978	4.5	0.20	89	37	<0.5	<5	2.34	32	8	99	194	3.44	<1	0.17	<10	0.60	1594	10	<0.01	4	0.042	1348	1.55	7	3	114	<5	<0.01	<10	19	9	<10	3151	2
83979	1.7	0.18	203	19	<0.5	<5	0.99	12	7	154	59	2.66	<1	0.13	<10	0.29	878	9	<0.01	4	0.038	333	1.45	5	1	48	<5	<0.01	<10	14	6	<10	1133	1
83979A	<0.2	0.95	<5	224	<0.5	<5	0.49	<1	6	122	<1	2.14	<1	0.49	<10	0.59	559	<2	0.07	6	0.075	6	<0.01	<5	2	43	<5	0.13	<10	<10	38	<10	61	2
83980	3.9	0.26	295	74	<0.5	<5	1.04	16	13	149	179	3.79	<1	0.21	<10	0.35	1087	11	<0.01	4	0.065	730	2.32	9	2	49	<5	<0.01	<10	15	12	<10	1793	2
83981	2.6	0.37	337	115	0.5	<5	3.21	4	20	41	154	5.25	<1	0.30	<10	0.99	2613	9	0.01	3	0.133	90	1.31	7	5	136	<5	<0.01	<10	22	31	<10	304	3
83982	6.0	0.36	334	70	<0.5	<5	2.77	3	15	64	96	4.63	<1	0.25	<10	0.81	2032	12	0.01	4	0.100	158	3.00	17	3	128	<5	<0.01	<10	21	23	<10	230	3
83983	3.1	0.84	148	94	<0.5	<5	3.13	2	16	46	151	4.80	<1	0.28	<10	1.12	2267	6	0.01	4	0.119	18	2.35	<5	4	119	<5	<0.01	<10	21	49	<10	91	3
83984	3.8	1.70	115	74	<0.5	<5	3.46	3	20	40	253	5.57	<1	0.25	<10	1.40	2369	10	0.01	4	0.134	16	2.33	<5	6	126	<5	0.01	<10	23	82	<10	147	4
83985	3.8	1.49	99	61	<0.5	<5	3.47	2	19	23	193	5.22	<1	0.25	<10	1.30	2275	13	0.01	3	0.127	11	1.47	<5	6	123	<5	<0.01	<10	22	85	<10	112	3
83986	2.6	0.42	118	87	0.5	<5	3.56	2	16	40	146	4.91	<1	0.30	<10	1.14	2676	7	0.01	3	0.118	26	1.76	6	5	168	<5	<0.01	<10	26	27	<10	124	3
83987	3.3	0.82	145	64	0.5	<5	3.10	3	19	24	167	5.43	<1	0.29	<10	1.18	3177	8	0.01	4	0.134	20	2.37	5	5	128	<5	<0.01	<10	27	48	<10	126	3
83988	2.6	0.40	116	76	0.5	<5	3.69	3	17	51	135	4.85	<1	0.33	<10	1.12	2867	6	0.01	3	0.118	53	2.23	6	4	149	<5	<0.01	<10	24	21	<10	155	3
83989	3.7	0.36	176	66	0.5	<5	4.08	3	19	52	135	5.33	<1	0.30	<10	1.06	4146	11	0.01	4	0.123	36	3.03	7	4	153	<5	<0.01	<10	31	20	<10	117	3
83990	2.8	0.30	230	59	<0.5	<5	2.64	4	12	90	115	4.41	<1	0.23	<10	0.72	2705	9	<0.01	3	0.087	49	2.72	7	3	104	<5	<0.01	<10	22	12	<10	344	3
83991	1.6	0.45	106	128	<0.5	<5	3.11	2	9	66	66	3.68	<1	0.24	<10	0.63	2786	3	0.01	3	0.082	43	1.88	5	3	74	<5	<0.01	<10	19	19	<10	161	2
83992	1.3	0.43	92	115	<0.5	<5	3.07	2	9	114	42	3.79	<1	0.26	<10	0.60	2293	9	0.01	3	0.078	41	1.94	6	3	92	<5	<0.01	<10	18	16	<10	128	2
83993	2.8	0.54	87	118	<0.5	<5	2.42	4	10	61	73	4.06	<1	0.26	<10	0.57	2352	31	0.01	3	0.089	350	1.86	<5	3	67	<5	<0.01	<10	17	23	<10	692	2
83994	1.3	0.36	63	145	<0.5	5	2.81	2	9	80	65	3.90	<1	0.26	<10	0.70	2744	15	0.01	5	0.090	33	1.33	5	3	97	<5	<0.01	<10	16	17	<10	154	2
83995	5.6	0.21	91	84	<0.5	<5	3.52	7	6	168	106	3.47	<1	0.17	<10	0.58	2167	7	<0.01	7	0.053	1151	2.11	11	2	110	<5	<0.01	<10	13	6	<10	1293	2
83996	1.3	0.24	66	45	<0.5	<5	3.12	2	6	117	38	3.67	<1	0.19	<10	0.88	2597	6	<0.01	5	0.066	83	0.91	7	3	152	<5	<0.01	<10	16	10	<10	179	2
83997	1.1	0.27	59	176	<0.5	<5	3.60	2	6	195	33	3.31	<1	0.21	<10	0.81	3003	7	<0.01	7	0.063	40	1.34	9	2	170	<5	<0.01	<10	14	7	<10	113	2
83998	3.2	0.22	80	82	<0.5	<5	3.56	2	5	154	31	2.59	<1	0.19	<10	0.28	2319	3	<0.01	6	0.049	356	1.68	7	1	126	<5	<0.01	<10	13	5	<10	426	2
83999	12.9	0.20	99	117	<0.5	<5	5.29	8	5	144	349	2.51	<1	0.15	<10	0.18	2300	3	<0.01	6	0.048	1508	2.15	9	1	97	<5	<0.01	<10	13	5	<10	1925	2
84000	2.6	0.21	149	54	<0.5	<5	4.10	2	6	103	90	2.73	<1	0.18	<10	0.13	1804	8	<0.01	5	0.058	244	2.41	6	1	66	<5	<0.01	<10	13	5	<10	383	2
84001	1.5	0.47	169	62	<0.5	<5	2.89	2	7	123	42	3.13	<1	0.18	<10	0.33	2166	8	<0.01	6	0.066	122	2.16	6	1	72	<5	<0.01	<10	12	15	<10	275	2
84002	1.5	0.51	145	145	<0.5	<5	4.24	2	7	84	69	3.32	<1	0.19	<10	0.47	2970	7	0.01	4	0.079	80	1.76	5	2	118	<5	<0.01	<10	18	21	<10	201	2
84003	1.8	0.30	837	80	<0.5	<5	4.11	3	6	107	63	3.08	<1	0.16	<10	0.28	2466	6	<0.01	4	0.065	105	2.34	14	1	99	<5	<0.01	<10	15	11	<10	307	2
84004	1.2	0.65	346	64	<0.5	<5	3.60	2	7	79	31	3.65	<1	0.15	<10	0.64	2972	13	<0.01	4	0.074	21	1.53	6	3	106	<5	<0.01	<10	17	26	<10	171	2
84005	3.3	0.87	280	65	<0.5	<5	4.53	10	7	133	61	3.41	<1	0.19	<10	0.69	3576	6	0.01	5	0.071	740	1.33	10	3	128	<5	<0.01	<10	19	29	<10	863	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2472RJ

Date : Jul-22-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/PO#shipment8

Multi-Element ICP-AES Analysis

Attention : Sue Deane

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84006	2.0	0.56	229	150	<0.5	<5	4.06	7	6	89	67	3.18	<1	0.17	<10	0.61	3376	19	<0.01	4	0.068	240	1.32	6	2	124	<5	<0.01	<10	17	21	<10	676	2
84007	3.7	0.32	189	87	<0.5	<5	5.52	3	8	125	38	4.10	<1	0.23	<10	0.76	4380	37	0.01	5	0.082	406	2.84	7	2	206	<5	<0.01	<10	26	17	<10	331	3
84008	3.3	0.23	106	109	<0.5	<5	4.33	5	6	108	54	3.02	<1	0.18	<10	0.49	3145	7	<0.01	5	0.058	702	1.92	7	2	170	<5	<0.01	<10	17	9	<10	709	2
84009	5.5	0.22	86	61	<0.5	<5	3.77	4	7	128	225	3.01	<1	0.20	<10	0.41	2683	16	<0.01	5	0.064	588	2.01	8	2	160	<5	<0.01	<10	14	7	<10	643	2
84010	6.6	0.28	129	105	<0.5	<5	4.74	6	7	91	49	3.11	<1	0.18	<10	0.37	2668	8	<0.01	4	0.061	724	2.04	5	2	170	<5	<0.01	<10	15	13	<10	829	2
84010A	>200.0	0.74	1904	88	<0.5	61	4.02	2	57	20	2325	2.95	1	0.07	<10	0.23	816	134	0.05	23	0.080	393	0.64	469	2	132	<5	0.03	<10	<10	17	17	299	7
84011	1.1	0.97	86	271	<0.5	<5	3.42	2	8	89	34	3.71	<1	0.21	<10	0.66	1694	17	0.01	4	0.086	32	0.89	5	3	140	<5	<0.01	<10	<10	31	<10	128	2
84012	0.4	1.37	18	167	<0.5	<5	2.99	2	8	60	26	3.72	<1	0.22	<10	0.79	1447	9	0.02	4	0.091	17	0.55	<5	3	156	<5	<0.01	<10	10	38	<10	132	2
84013	0.9	0.89	23	63	<0.5	<5	3.63	2	7	77	38	3.98	<1	0.20	<10	0.84	1915	21	0.02	4	0.083	67	0.71	5	4	294	<5	<0.01	<10	12	20	<10	142	2
84014	0.5	1.05	24	73	<0.5	<5	3.28	3	7	51	29	3.83	<1	0.22	<10	0.78	1548	21	0.02	3	0.085	17	0.64	<5	4	388	<5	<0.01	<10	11	26	<10	243	2
84015	0.4	1.44	21	88	<0.5	<5	2.77	3	8	63	33	4.02	<1	0.21	<10	0.81	1471	7	0.02	3	0.090	47	0.63	<5	4	142	<5	<0.01	<10	11	36	<10	288	3
84016	<0.2	0.87	<5	426	<0.5	<5	2.58	1	6	37	<1	1.97	<1	0.25	16	0.57	477	<2	0.03	4	0.088	16	0.06	<5	2	120	<5	<0.01	<10	<10	21	<10	48	4
84017	0.6	1.14	23	72	<0.5	<5	3.93	1	7	51	48	3.10	<1	0.19	<10	0.64	1335	33	0.01	3	0.085	139	0.58	<5	3	125	<5	<0.01	<10	11	26	<10	98	2
84018	1.0	1.31	119	300	<0.5	<5	3.49	2	8	42	62	3.57	<1	0.19	<10	0.76	1566	6	0.01	3	0.090	67	0.75	5	3	89	<5	<0.01	<10	12	36	<10	165	2
84019	<0.2	0.99	8	58	<0.5	<5	3.01	1	6	42	<1	2.14	<1	0.26	<10	0.64	874	<2	0.02	5	0.069	3	0.36	<5	3	114	<5	<0.01	<10	<10	21	<10	42	3
84020	<0.2	1.28	<5	427	0.5	<5	2.81	1	8	62	26	3.25	<1	0.33	11	0.92	942	36	0.03	3	0.076	7	0.19	<5	5	117	<5	0.02	<10	<10	49	<10	92	3
84021	<0.2	0.91	<5	898	<0.5	<5	2.55	<1	5	51	<1	1.69	<1	0.25	12	0.62	536	<2	0.03	5	0.063	2	0.09	<5	2	107	<5	<0.01	<10	<10	19	<10	34	4
84022	0.9	1.64	10	106	<0.5	<5	2.66	1	13	29	158	3.79	<1	0.21	<10	0.91	1257	45	0.02	4	0.102	9	0.27	<5	3	67	<5	0.10	<10	11	67	<10	111	3
84023	0.5	1.80	<5	92	<0.5	<5	2.92	1	13	30	197	4.50	<1	0.14	<10	0.92	1439	15	0.03	4	0.102	3	0.09	<5	3	65	<5	0.10	<10	16	72	<10	143	3
84024	6.4	0.31	549	131	<0.5	<5	0.20	4	6	68	59	2.38	<1	0.16	<10	0.15	394	19	0.01	3	0.047	335	1.57	11	1	4	<5	<0.01	<10	<10	10	<10	498	2
84025	6.6	0.71	164	122	<0.5	<5	0.34	3	9	52	177	3.92	<1	0.18	<10	0.47	1084	15	0.01	3	0.081	22	1.82	6	2	10	<5	<0.01	<10	10	35	<10	216	3
84026	<0.2	0.90	<5	226	<0.5	<5	0.42	<1	6	109	<1	2.04	<1	0.49	<10	0.57	534	<2	0.07	6	0.074	2	<0.01	<5	2	32	5	0.12	<10	<10	36	<10	45	2
84027	>200.0	0.69	1914	89	<0.5	63	3.85	2	57	20	2337	2.86	1	0.08	<10	0.22	781	130	0.05	23	0.080	374	0.63	460	1	122	<5	0.02	<10	11	16	19	280	7
84028	7.0	1.21	277	84	<0.5	6	0.30	6	16	45	298	5.03	<1	0.21	<10	0.63	1263	18	0.01	5	0.089	56	2.52	9	3	4	<5	<0.01	<10	14	74	<10	513	3
84029	4.8	1.40	198	100	<0.5	6	0.27	3	14	44	173	5.03	<1	0.21	<10	0.68	1483	20	0.01	4	0.089	34	2.04	8	4	3	<5	<0.01	<10	15	86	<10	318	3
84030	4.2	1.70	102	115	<0.5	5	0.52	3	16	38	247	5.00	<1	0.22	<10	0.99	1919	17	0.01	5	0.101	36	1.18	<5	5	17	<5	<0.01	<10	14	95	<10	241	3
84031	4.0	0.83	156	106	<0.5	<5	0.55	2	14	51	288	4.28	<1	0.22	<10	0.66	1533	11	0.01	4	0.080	27	1.34	5	3	26	<5	<0.01	<10	15	44	<10	179	2
84032	3.3	0.66	170	128	<0.5	<5	0.57	4	9	65	158	3.64	<1	0.17	<10	0.50	1423	14	0.01	3	0.072	41	1.47	6	2	27	<5	<0.01	<10	<10	34	<10	397	2
84033	4.7	0.86	279	120	<0.5	6	0.93	2	12	46	257	4.32	<1	0.18	<10	0.60	1894	16	0.01	3	0.093	25	1.61	6	4	34	<5	<0.01	<10	15	48	<10	201	3
84034	6.2	0.24	316	32	<0.5	13	0.66	4	10	71	175	8.27	<1	0.22	<10	0.24	871	10	0.01	4	0.078	45	8.35	22	2	29	<5	<0.01	<10	28	14	<10	134	5

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2472RJ

Date : Jul-22-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/PO#shipment8

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Attention : Sue Deane

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84035	3.6	0.25	203	87	<0.5	6	0.68	5	14	68	101	4.15	<1	0.23	<10	0.40	1349	5	0.01	4	0.085	35	2.34	8	2	39	<5	<0.01	<10	16	15	<10	495	2
84036	3.3	0.26	173	118	<0.5	5	1.53	3	12	70	133	4.05	<1	0.20	<10	0.53	1494	12	0.01	4	0.084	37	2.17	7	3	132	<5	<0.01	<10	17	16	<10	237	2
84037	3.4	0.29	141	104	<0.5	<5	0.59	3	12	93	157	3.45	<1	0.20	<10	0.32	939	8	0.01	4	0.077	19	1.89	7	2	45	<5	<0.01	<10	12	18	<10	313	2
84038	2.1	0.58	119	169	<0.5	5	0.67	3	16	41	116	4.82	<1	0.28	<10	0.67	2174	18	0.01	4	0.111	25	1.33	7	4	38	5	<0.01	<10	16	32	<10	282	3
84039	5.1	0.42	268	114	<0.5	<5	0.60	4	13	63	110	4.37	<1	0.20	<10	0.44	1473	11	0.01	3	0.089	36	2.31	7	3	44	<5	<0.01	<10	16	31	<10	461	2
84040	8.4	0.35	391	60	<0.5	7	0.18	40	10	75	117	4.96	<1	0.19	<10	0.15	298	6	<0.01	3	0.052	2171	4.82	8	1	<1	<5	<0.01	<10	14	18	<10	5113	3
84041	17.9	0.21	238	40	<0.5	10	0.15	80	6	94	173	5.78	<1	0.14	<10	0.10	227	5	<0.01	3	0.034	8036	6.26	10	<1	3	<5	<0.01	<10	15	6	<10	>10000	3
84042	8.6	0.26	195	56	<0.5	8	0.40	36	7	91	76	5.07	<1	0.17	<10	0.16	377	8	0.01	3	0.050	1304	4.75	8	1	16	<5	<0.01	<10	11	7	<10	4685	3
84042A	10.5	0.26	153	54	<0.5	8	1.72	35	7	81	291	5.54	<1	0.19	<10	0.54	1314	4	0.01	4	0.062	2157	4.04	8	2	96	<5	<0.01	<10	19	9	<10	4320	4
84043	1.2	0.21	39	195	<0.5	<5	1.03	3	6	99	20	3.38	<1	0.20	<10	0.44	941	6	0.01	3	0.061	222	1.14	7	2	74	<5	<0.01	<10	<10	5	<10	328	2
84044	0.9	0.23	42	200	<0.5	5	1.03	2	7	109	35	3.40	<1	0.20	<10	0.44	851	4	0.01	4	0.061	26	1.13	8	2	82	<5	<0.01	<10	<10	6	<10	157	2
84045	0.3	0.22	12	380	<0.5	<5	2.34	2	6	91	16	3.44	<1	0.21	<10	0.67	1241	6	0.02	3	0.067	9	0.46	5	3	238	<5	<0.01	<10	11	6	<10	126	2
84046	0.3	0.29	71	299	<0.5	5	2.07	2	8	74	10	3.52	<1	0.24	<10	0.50	1252	11	0.01	3	0.074	8	0.76	5	3	91	<5	<0.01	<10	<10	7	<10	125	2
84047	0.2	0.86	69	94	<0.5	6	2.22	2	7	84	11	3.60	<1	0.19	<10	0.56	1287	18	0.01	3	0.068	6	1.00	5	3	104	<5	<0.01	<10	<10	23	<10	160	2
84048	0.2	0.22	40	282	<0.5	<5	1.75	1	6	95	7	3.23	<1	0.20	<10	0.52	1157	7	0.01	3	0.058	43	0.84	5	2	86	<5	<0.01	<10	<10	9	<10	107	2
84049	0.2	0.24	17	93	<0.5	<5	1.61	1	7	81	9	3.36	<1	0.21	<10	0.61	1234	7	0.01	3	0.073	22	0.39	5	2	60	<5	<0.01	<10	<10	11	<10	102	2
84050	0.4	0.37	150	78	<0.5	<5	1.64	1	6	96	16	3.09	<1	0.20	<10	0.46	945	6	0.01	4	0.065	7	0.66	6	2	72	<5	<0.01	<10	<10	13	<10	76	2
84051	0.3	0.23	43	173	<0.5	5	1.52	1	6	111	24	3.04	<1	0.19	<10	0.43	886	5	0.01	3	0.055	6	0.96	6	2	52	<5	<0.01	<10	<10	11	<10	65	2
84052	0.3	0.23	48	104	<0.5	<5	2.33	1	5	96	5	3.19	<1	0.20	<10	0.51	1199	3	0.01	4	0.061	134	0.98	6	2	99	<5	<0.01	<10	<10	11	<10	100	2
84053	0.3	0.46	44	57	<0.5	5	1.64	1	6	107	1	2.88	<1	0.17	<10	0.40	903	7	0.01	3	0.056	6	0.57	5	2	57	<5	<0.01	<10	<10	17	<10	60	2
84054	<0.2	0.44	79	210	<0.5	5	2.78	1	5	96	<1	3.04	<1	0.19	<10	0.37	1066	3	0.01	3	0.051	11	1.04	5	2	106	<5	<0.01	<10	11	11	<10	60	2
84055	0.3	0.57	63	56	<0.5	<5	1.47	1	5	103	<1	2.76	<1	0.17	<10	0.34	728	10	0.01	3	0.049	6	0.79	5	1	59	<5	<0.01	<10	<10	15	<10	52	2
84056	2.0	0.15	368	82	<0.5	6	3.35	1	5	110	<1	3.80	<1	0.15	<10	0.05	1097	8	<0.01	4	0.036	30	2.76	15	1	44	<5	<0.01	<10	13	3	<10	22	2
84057	0.2	0.32	42	120	<0.5	<5	2.17	1	5	112	10	2.56	<1	0.18	<10	0.40	933	5	0.01	3	0.051	5	0.68	5	2	79	<5	<0.01	<10	<10	10	<10	56	2
84058	<0.2	0.29	60	66	<0.5	<5	2.04	1	6	102	7	2.65	<1	0.18	<10	0.43	855	8	0.01	3	0.054	4	0.84	5	2	90	<5	<0.01	<10	<10	10	<10	62	2
84058A	<0.2	0.90	<5	223	<0.5	<5	0.44	<1	6	127	<1	2.03	<1	0.47	<10	0.56	532	2	0.07	6	0.070	<2	<0.01	<5	2	36	7	0.12	<10	<10	36	<10	44	2
84059	<0.2	0.51	95	45	<0.5	<5	1.33	1	6	72	5	3.00	<1	0.17	<10	0.48	865	5	0.01	3	0.064	4	0.95	<5	2	57	<5	<0.01	<10	<10	14	<10	64	2
84060	0.6	0.23	110	50	<0.5	<5	1.26	1	8	103	7	3.41	<1	0.20	<10	0.45	832	5	0.01	3	0.069	7	1.32	7	2	50	<5	<0.01	<10	<10	10	<10	75	2
84061	0.3	0.19	61	312	<0.5	<5	2.53	1	5	93	1	2.60	<1	0.17	<10	0.46	1045	4	0.01	3	0.053	5	0.73	5	2	76	<5	<0.01	<10	<10	7	<10	39	2
84062	0.3	0.18	77	62	<0.5	<5	0.62	1	5	120	8	2.45	<1	0.17	<10	0.15	574	9	0.01	3	0.045	9	0.84	6	1	14	<5	<0.01	<10	<10	4	<10	56	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2472RJ

Date : Jul-22-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/PO#shipment8

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84063	1.5	0.17	139	116	<0.5	<5	1.66	4	6	103	19	3.34	<1	0.17	<10	0.21	879	8	0.01	4	0.049	365	1.59	6	1	70	<5	<0.01	<10	<10	6	<10	398	2
84064	1.9	0.18	192	122	<0.5	<5	2.67	5	4	107	8	2.22	<1	0.14	<10	0.04	988	7	<0.01	3	0.035	663	0.61	5	1	26	<5	<0.01	<10	<10	4	<10	757	2
84065	0.4	0.19	123	122	<0.5	5	0.81	1	5	99	1	2.87	<1	0.16	<10	0.06	572	5	0.01	4	0.046	15	0.99	5	1	19	<5	<0.01	<10	<10	6	<10	68	2
84066	0.3	0.16	107	55	<0.5	<5	1.70	1	5	105	3	2.76	<1	0.17	<10	0.26	683	6	0.01	3	0.048	15	1.38	5	1	55	<5	<0.01	<10	<10	4	<10	80	2
84067	<0.2	0.38	46	273	<0.5	<5	2.19	1	5	92	4	2.82	<1	0.18	<10	0.47	996	3	0.01	3	0.055	4	0.72	<5	2	85	<5	<0.01	<10	<10	13	<10	60	2
84068	0.5	0.30	96	55	<0.5	<5	5.16	2	6	71	18	2.98	<1	0.25	<10	0.43	1582	5	0.01	2	0.071	65	1.32	5	2	184	<5	<0.01	<10	12	8	<10	140	2
84069	<0.2	0.82	64	73	<0.5	<5	2.21	1	8	50	13	3.71	<1	0.24	<10	0.74	1222	4	0.01	3	0.093	7	0.86	<5	3	91	<5	<0.01	<10	10	24	<10	80	3
84070	0.6	0.64	134	166	<0.5	<5	3.84	1	7	58	8	3.29	<1	0.23	<10	0.58	1345	6	0.01	3	0.079	134	1.35	<5	3	135	<5	<0.01	<10	10	17	<10	101	2
84071	0.2	0.94	49	80	<0.5	<5	2.85	1	7	40	20	3.58	<1	0.20	<10	0.78	1392	5	0.01	2	0.088	7	0.65	<5	3	79	<5	<0.01	<10	<10	31	<10	75	2
84072	0.5	0.27	117	124	<0.5	<5	2.68	2	7	92	16	3.20	<1	0.24	<10	0.42	1150	12	0.01	3	0.069	21	1.42	5	2	117	<5	<0.01	<10	12	6	<10	85	2
84073	0.4	0.23	44	113	<0.5	<5	2.30	2	8	64	23	3.49	<1	0.22	<10	0.63	1291	2	0.01	3	0.075	9	0.95	<5	2	104	<5	<0.01	<10	12	7	<10	93	2
84074	0.4	0.22	52	294	<0.5	<5	2.38	2	8	93	20	3.87	<1	0.23	<10	0.76	1639	4	0.01	3	0.073	16	0.79	<5	3	127	<5	<0.01	<10	13	7	<10	114	2
84075	0.5	0.25	34	173	<0.5	<5	1.52	2	8	83	23	3.72	<1	0.23	<10	0.63	1240	3	0.01	4	0.088	15	0.70	<5	3	120	<5	<0.01	<10	<10	8	<10	159	2
84076	3.6	0.22	819	56	<0.5	6	2.04	23	9	89	56	5.07	<1	0.21	<10	0.53	1167	4	0.01	4	0.064	522	3.31	11	2	227	<5	<0.01	<10	19	7	<10	1867	3
84077	0.8	0.47	108	61	<0.5	7	0.66	7	8	76	41	5.57	<1	0.21	<10	0.51	923	<2	0.01	4	0.072	25	3.49	8	2	36	<5	<0.01	<10	14	17	<10	712	3
84078	3.3	0.20	144	18	<0.5	27	0.38	7	5	92	13	14.71	<1	0.16	<10	0.28	498	<2	0.01	4	0.048	39	>10.00	25	<1	26	<5	<0.01	<10	56	14	<10	236	9
84079	0.6	0.59	90	48	<0.5	9	0.49	3	7	81	14	6.85	<1	0.18	<10	0.48	774	<2	0.01	4	0.068	17	5.44	10	2	25	<5	<0.01	<10	20	20	<10	95	4
84080	1.5	0.30	157	18	<0.5	23	0.45	5	5	103	4	13.13	<1	0.16	<10	0.39	603	<2	0.01	4	0.050	19	>10.00	20	<1	31	<5	<0.01	<10	48	17	<10	78	8
84081	2.4	0.17	192	17	<0.5	37	0.36	9	4	74	13	18.18	<1	0.14	<10	0.29	425	<2	0.01	5	0.040	35	>10.00	34	<1	28	<5	<0.01	<10	83	15	<10	62	13
84082	2.6	0.59	124	46	<0.5	11	1.41	6	7	105	35	8.09	<1	0.17	<10	0.67	1253	3	0.01	4	0.064	1555	6.58	12	2	63	<5	<0.01	<10	23	22	<10	462	5
84083	0.9	0.54	34	62	<0.5	5	1.20	8	8	72	32	4.38	<1	0.21	<10	0.56	967	2	0.01	3	0.086	78	1.88	6	2	50	<5	<0.01	<10	10	14	<10	984	3
84084	0.2	0.84	30	61	<0.5	<5	0.81	1	7	93	5	3.45	<1	0.19	<10	0.58	856	4	0.01	3	0.079	11	0.84	5	2	33	<5	<0.01	<10	<10	23	<10	82	2
84085	<0.2	0.93	<5	229	<0.5	<5	0.43	<1	6	114	<1	2.15	<1	0.49	<10	0.58	540	<2	0.07	6	0.072	2	0.01	<5	2	43	<5	0.12	<10	<10	37	<10	47	2
84086	175.3	0.74	213	180	<0.5	110	4.73	3	16	21	4169	3.39	5	0.18	<10	0.19	562	82	0.03	36	0.065	224	1.44	279	2	182	<5	0.05	<10	<10	19	25	260	9
84087	0.3	0.82	62	47	<0.5	<5	0.99	2	7	85	20	4.49	<1	0.17	<10	0.62	976	3	0.01	3	0.074	8	2.12	10	2	42	<5	<0.01	<10	14	28	<10	76	3
84088	0.4	0.65	62	46	<0.5	<5	0.99	1	7	94	10	3.86	<1	0.18	<10	0.57	891	2	0.01	4	0.063	7	1.68	6	2	40	<5	<0.01	<10	11	24	<10	48	2
84089	0.2	0.88	42	140	<0.5	<5	1.81	1	8	75	8	3.77	<1	0.23	<10	0.74	1219	10	0.01	3	0.086	7	0.95	<5	3	66	<5	<0.01	<10	<10	32	<10	60	2
84090	0.2	0.28	49	77	<0.5	<5	1.72	2	8	108	13	3.70	<1	0.19	<10	0.61	1288	2	0.01	4	0.076	6	0.76	<5	3	87	<5	<0.01	<10	<10	19	<10	97	2
84091	0.5	0.27	33	164	<0.5	<5	1.84	2	8	108	18	3.89	<1	0.21	<10	0.69	1305	5	0.01	3	0.080	6	0.90	5	3	113	<5	<0.01	<10	12	18	<10	90	2
84092	0.3	0.24	50	151	<0.5	<5	1.82	2	7	143	19	3.82	<1	0.18	<10	0.64	1185	5	0.01	4	0.068	5	1.14	7	3	110	<5	<0.01	<10	13	16	<10	80	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2472RJ

Date : Jul-22-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/PO#shipment8

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84093	0.9	0.24	63	76	<0.5	6	1.96	3	7	99	72	4.78	<1	0.20	<10	0.62	1154	2	0.01	4	0.071	19	2.38	6	3	108	<5	<0.01	<10	17	15	<10	175	3
84094	<0.2	0.31	32	57	<0.5	<5	1.84	1	8	97	14	3.86	<1	0.22	<10	0.71	1224	4	0.02	3	0.083	5	0.63	<5	3	99	<5	<0.01	<10	10	23	<10	69	2
84095	0.3	0.25	37	248	<0.5	<5	2.40	2	7	93	19	3.43	<1	0.20	<10	0.65	1134	6	0.01	3	0.067	10	0.87	<5	2	130	<5	<0.01	<10	<10	15	<10	81	2
84096	0.2	0.93	15	90	<0.5	5	3.62	2	9	76	38	4.03	<1	0.17	<10	0.73	1508	5	0.02	3	0.089	7	0.41	<5	4	153	<5	<0.01	<10	13	43	<10	91	2
84097	<0.2	1.12	8	103	<0.5	<5	2.74	1	9	59	22	3.97	<1	0.18	<10	0.75	1172	3	0.02	3	0.093	6	0.37	<5	3	89	<5	<0.01	<10	<10	46	<10	79	2
84098	<0.2	1.09	24	69	<0.5	<5	2.24	2	9	68	22	3.92	<1	0.22	<10	0.73	1101	17	0.02	3	0.097	5	0.80	5	3	63	<5	<0.01	<10	<10	40	<10	124	2
84099	0.4	1.17	24	49	<0.5	5	1.80	2	11	47	9	5.17	<1	0.16	<10	0.82	1055	3	0.02	4	0.106	5	1.73	5	3	60	<5	<0.01	<10	13	48	<10	153	3
84100	0.2	0.49	340	98	0.5	5	2.13	2	13	73	12	4.76	<1	0.27	<10	0.76	1484	5	0.02	3	0.116	8	0.61	5	3	111	<5	<0.01	<10	13	28	<10	193	3
84101	0.2	1.34	31	75	<0.5	<5	2.43	2	12	39	14	4.66	<1	0.22	<10	0.93	1246	4	0.02	3	0.111	5	0.62	<5	3	88	<5	<0.01	<10	10	50	<10	120	2
84102	<0.2	1.14	22	88	<0.5	<5	3.62	2	11	52	22	4.34	<1	0.21	<10	0.82	1295	7	0.02	3	0.108	5	0.57	<5	3	117	<5	<0.01	<10	10	47	<10	188	3
84103	0.3	0.41	24	186	<0.5	<5	2.96	2	12	52	31	4.19	<1	0.30	<10	0.78	1342	8	0.02	3	0.128	6	0.39	<5	4	186	<5	<0.01	<10	13	25	<10	151	2
84104	<0.2	1.20	10	112	<0.5	<5	3.06	2	9	70	15	3.87	<1	0.23	<10	0.76	1228	4	0.02	3	0.090	3	0.39	<5	3	157	<5	<0.01	<10	<10	37	<10	214	2
84105	<0.2	1.47	10	256	<0.5	<5	3.70	2	10	47	15	4.17	<1	0.20	<10	1.02	1563	3	0.02	3	0.109	2	0.24	<5	4	209	<5	0.01	<10	11	44	<10	151	3
84106	<0.2	1.52	26	210	<0.5	<5	3.68	2	11	49	33	4.28	<1	0.19	<10	0.88	1397	6	0.02	3	0.115	3	0.53	<5	3	145	<5	0.02	<10	11	50	<10	135	3
84107	<0.2	0.88	16	299	<0.5	<5	3.48	2	9	51	22	3.72	<1	0.24	<10	0.89	1474	3	0.02	3	0.088	4	0.48	<5	4	259	<5	<0.01	<10	10	31	<10	146	2
84108	<0.2	1.38	7	140	<0.5	<5	3.07	1	9	69	19	3.60	<1	0.18	<10	0.82	1188	9	0.03	3	0.089	3	0.30	<5	4	100	<5	0.02	<10	<10	44	<10	99	3
84109	<0.2	1.32	17	97	<0.5	<5	3.14	1	8	52	11	3.55	<1	0.19	<10	0.79	1247	7	0.02	3	0.081	10	0.50	<5	3	114	<5	<0.01	<10	10	41	<10	94	2
84110	1.1	1.55	41	142	<0.5	<5	0.91	2	12	28	21	4.19	<1	0.24	10	0.80	1099	4	0.02	4	0.110	15	1.11	<5	2	45	<5	0.01	<10	<10	29	<10	85	3
84111	3.6	1.25	262	144	<0.5	<5	1.63	2	8	30	34	3.78	<1	0.34	<10	0.44	1281	14	0.01	3	0.108	60	1.31	10	2	56	<5	<0.01	<10	16	23	<10	132	2
84112	2.6	1.55	82	153	<0.5	<5	1.28	2	12	25	20	4.57	<1	0.34	<10	0.59	1468	7	0.01	4	0.119	61	1.50	7	2	44	<5	<0.01	<10	14	29	<10	159	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Quality Assaying for over 35 Years

Assay Certificate

8V-2508-RA1


Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment9**
Attn: **Sue Deane**

Jul-30-08

We hereby certify the following assay of 24 core samples submitted Jul-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84113	0.07	0.08	2.5
84114	0.14		3.2
84115	0.07		3.4
84116	0.05		1.5
84117	0.10		1.4
84118	0.28		4.6
84119	0.16		1.8
84120	0.32		1.4
84121	0.20		2.7
84122	0.30	0.28	2.5
84123	0.23		1.9
84124	0.25		2.1
84125	0.26		1.6
84126	0.32		0.9
84127	0.22		0.4
84128	0.41		1.8
84129	0.47		1.0
84130	0.24		1.9
84131	0.25		1.1
84132	0.27	0.25	0.5
84133	0.19		0.3
84134	0.27		0.9
84135	<0.01		<0.2
84136	0.22		1.2
*0218	0.89		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 35 Years

Assay Certificate

8V-2508-RA2


Company: **Ascot Resources Ltd**
 Project: **Dilworth/PO#shipment9**
 Attn: **Sue Deane**

Jul-30-08

We hereby certify the following assay of 24 core samples submitted Jul-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
84137	0.13	0.13	<0.2	
84138	0.18		<0.2	
84139	0.25		<0.2	
84140	0.25		0.7	
84141	0.21		0.6	
84142	0.32		<0.2	
84143	0.22		<0.2	
84144	0.19		0.5	
84145	0.24		0.2	
84146	0.26	0.27	<0.2	
84147	0.18		1.5	
84148	0.45		1.8	
84149	0.47		1.0	
84150	0.15		1.6	
84151	0.38		3.8	
84152	0.31		1.0	
84153	0.63		6.0	
84154	0.71		3.6	
84155	1.31		>200	232.5
84156	0.18	0.16	1.7	
84157	0.60		1.1	
84158	0.79		1.7	
84159	4.80		1.9	
84160	0.34		1.0	
*0218	0.89			
*CCu-1c				131.9
*BLANK	<0.01			<0.1

Certified by _____ 



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 35 Years

Assay Certificate

8V-2508-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment9**
Attn: **Sue Deane**

Jul-30-08

We *hereby certify* the following assay of 24 core samples submitted Jul-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84161	0.29	0.33	2.6
84162	0.16		1.9
84163	0.43		2.1
84164	0.94		3.2
84165	4.98		6.0
84166	0.84		2.5
84167	0.28		1.4
84168	0.46		1.4
84169	0.85		2.4
84170	0.45	0.42	1.9
84171	0.53		1.5
84172	1.10		1.8
84173	0.81		3.0
84174	0.89		1.6
84175	0.62		2.2
84176	0.78		1.2
84177	0.57		2.4
84178	0.49		2.7
84179	0.65		4.2
84180	<0.01	0.01	0.2
84181	0.67		1.4
84182	0.69		1.6
84183	0.39		2.2
84184	0.95		4.3
*0218	0.89		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 35 Years

Assay Certificate

8V-2508-RA4

Company: **Ascot Resources Ltd**
 Project: **Dilworth/PO#shipment9**
 Attn: **Sue Deane**

Jul-30-08

We hereby certify the following assay of 24 core samples submitted Jul-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne	ZN %
84185	1.34	1.44	5.8		
84186	0.73		3.9		
84187	0.65		2.1		
84188	0.77		2.0		
84189	1.08		3.3		
84190	0.70		5.3		
84191	0.92		2.0		
84192	0.60		3.9		
84193	0.46		5.2		
84194	0.42	0.45	1.3		
84195	0.44		3.3		
84196	0.36		2.1		
84197	0.31		1.5		
84198	0.27		1.3		
84199	0.26		1.4		
84200	1.24		>200	225.8	
84201	0.22		1.2		
84202	0.18		3.5		
84203	0.38		4.0		
84204	0.33	0.34	3.5		1.12
84205	0.33		7.2		1.13
84206	0.26		9.4		1.13
84207	0.11		1.6		
84208	0.22		10.8		
*0218	0.88				
*CCu-1c				130.4	3.96
*BLANK	<0.01			<0.1	<0.01

Certified by _____ 

*Quality Assaying for over 35 Years***Assay Certificate****8V-2508-RA5**Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment9**
Attn: **Sue Deane****Jul-30-08**We *hereby certify* the following assay of 24 core samples
submitted Jul-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84209	0.24	0.26	5.4
84210	0.33		1.2
84211	0.19		0.7
84212	0.71		1.0
84213	0.04		0.5
84214	0.12		2.4
84215	0.28		1.4
84216	0.53		1.7
84217	0.34		3.0
84218	0.17	0.18	<0.2
84219	0.45		1.4
84220	0.26		0.6
84221	0.31		0.6
84222	0.80		6.1
84223	0.22		8.7
84224	0.16		1.4
84225	0.01		<0.2
84226	0.23		3.5
84227	0.15		8.5
84228	0.22	0.20	4.7
84229	0.25		3.5
84230	0.29		2.1
84231	0.24		1.2
84232	0.15		1.3
*0218	0.88		
*BLANK	<0.01		

Certified by _____

*Quality Assaying for over 35 Years***Assay Certificate****8V-2508-RA6**Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment9**
Attn: **Sue Deane****Jul-30-08**

We hereby certify the following assay of 17 core samples
submitted Jul-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84233	0.24	0.25	1.6
84234	0.05		2.7
84235	0.31		3.0
SD08-04	0.01		3.3
139024	0.15		14.0
139025	0.25		27.6
139026	0.49		49.4
139027	0.18		17.6
139028	0.20		15.4
139029	0.27	0.27	17.2
139030	0.23		10.8
139031	0.35		23.6
139032	0.42		40.5
139033	0.46		26.6
139034	0.15		16.5
139035	0.41		115.6
*0218	0.90		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St., Vancouver, B.C., V5X 4R6
 Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2508RJ

Date : Jul-30-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/PO#shipment9

Attention : Sue Deane

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84113	2.5	1.36	104	145	<0.5	<5	3.95	2	12	47	79	3.61	<1	0.35	<10	0.88	1650	5	0.02	6	0.098	34	1.71	5	4	165	<5	0.02	<10	<10	63	<10	129	2
84114	3.2	1.25	120	144	<0.5	<5	3.54	3	12	43	61	3.60	<1	0.35	<10	0.43	1569	5	0.01	4	0.094	153	1.47	<5	2	126	<5	<0.01	<10	<10	26	<10	308	2
84115	3.4	1.80	132	177	<0.5	<5	3.13	3	11	28	126	5.15	<1	0.35	<10	0.64	1900	12	0.01	4	0.097	82	1.48	5	2	108	<5	<0.01	<10	<10	36	<10	227	3
84116	1.5	1.64	24	160	<0.5	<5	3.72	2	11	38	79	3.47	<1	0.33	10	0.75	1872	11	0.01	4	0.093	49	0.31	<5	2	138	<5	<0.01	<10	<10	29	<10	111	2
84117	1.4	1.21	57	152	<0.5	<5	3.46	1	9	34	71	2.82	<1	0.38	<10	0.44	1443	10	0.01	4	0.082	48	0.69	<5	2	101	<5	<0.01	<10	<10	22	<10	155	2
84118	4.6	0.67	196	111	<0.5	<5	3.79	6	10	76	115	3.32	<1	0.20	<10	0.26	1371	45	0.01	4	0.049	381	2.45	8	2	63	<5	0.01	<10	<10	30	<10	676	2
84119	1.8	1.41	54	179	<0.5	<5	3.56	1	14	24	106	3.63	<1	0.32	<10	0.66	1735	8	0.01	3	0.095	32	0.98	<5	3	70	<5	0.01	<10	<10	53	<10	136	2
84120	1.4	1.27	138	135	<0.5	<5	7.28	2	18	33	96	3.99	<1	0.27	<10	0.65	2390	10	0.01	3	0.088	24	1.84	<5	3	131	<5	<0.01	<10	<10	48	<10	126	2
84121	2.7	0.53	164	95	<0.5	<5	4.66	2	10	36	84	3.06	<1	0.25	<10	0.31	1563	11	0.01	3	0.069	51	2.44	6	1	153	<5	<0.01	<10	<10	22	<10	122	2
84122	2.5	1.03	171	120	<0.5	<5	4.87	2	13	47	118	3.90	<1	0.39	<10	0.61	1995	7	0.01	3	0.089	25	2.15	<5	2	161	<5	<0.01	<10	<10	28	<10	190	2
84123	1.9	1.78	65	130	<0.5	<5	3.82	2	14	29	156	4.62	<1	0.36	<10	0.98	2010	8	0.01	3	0.103	12	1.17	<5	3	133	<5	<0.01	<10	<10	61	<10	164	3
84124	2.1	1.98	34	127	0.5	<5	4.04	2	16	19	231	4.77	<1	0.31	<10	1.02	2281	8	0.02	2	0.104	14	0.61	<5	4	113	<5	0.03	<10	<10	75	<10	170	3
84125	1.6	1.96	36	174	0.5	<5	4.17	2	16	43	207	4.59	<1	0.32	<10	0.98	2142	6	0.02	4	0.107	23	0.63	<5	4	108	<5	0.04	<10	<10	73	<10	229	3
84126	0.9	1.91	8	104	0.8	<5	2.86	2	20	35	206	4.31	<1	0.09	<10	1.02	1225	31	0.04	3	0.104	17	0.38	<5	4	145	<5	0.17	<10	<10	87	<10	221	6
84127	0.4	2.05	<5	69	0.8	<5	3.21	2	18	34	106	4.27	<1	0.14	<10	1.15	1387	4	0.04	3	0.108	5	0.24	<5	4	152	<5	0.17	<10	<10	87	<10	224	5
84128	1.8	2.02	59	143	0.7	<5	3.68	2	17	20	152	4.78	<1	0.27	<10	1.16	2185	3	0.02	2	0.103	31	0.71	<5	4	77	<5	0.10	<10	<10	82	<10	237	4
84129	1.0	2.62	13	657	1.0	<5	6.18	3	25	40	202	5.90	<1	0.21	10	1.63	2885	32	0.03	2	0.138	24	0.41	<5	7	256	<5	0.18	<10	<10	119	<10	248	7
84130	1.9	2.06	15	70	0.6	<5	6.06	2	18	13	249	4.96	<1	0.18	<10	1.28	2619	6	0.03	2	0.102	24	0.70	<5	4	118	<5	0.07	<10	<10	88	<10	215	4
84131	1.1	2.03	30	119	<0.5	<5	3.37	4	18	24	129	5.32	<1	0.20	<10	1.23	1967	4	0.03	2	0.105	37	0.98	<5	4	104	<5	0.05	<10	<10	92	<10	396	3
84132	0.5	2.27	12	182	1.0	<5	2.63	3	19	20	119	5.26	1	0.23	<10	1.38	1588	11	0.05	<1	0.117	26	0.26	<5	7	118	6	0.21	<10	<10	113	<10	310	5
84133	0.3	1.39	35	82	<0.5	<5	4.62	1	10	45	54	3.27	<1	0.21	10	0.80	1907	7	0.03	3	0.076	18	0.57	<5	4	57	<5	0.06	<10	<10	44	<10	119	3
84134	0.9	1.53	26	81	0.6	<5	3.31	1	12	53	87	3.58	<1	0.26	10	0.81	1798	20	0.02	3	0.087	11	0.53	<5	4	50	<5	0.09	<10	<10	44	<10	131	3
84135	<0.2	0.97	<5	349	0.6	<5	0.56	1	7	118	<1	2.01	<1	0.48	<10	0.59	571	<2	0.07	7	0.065	19	0.02	<5	2	61	5	0.12	<10	<10	39	<10	90	2
84136	1.2	2.25	22	86	1.1	<5	3.49	2	22	28	264	5.10	<1	0.34	<10	1.27	1879	18	0.02	2	0.119	9	0.60	<5	5	61	<5	0.20	<10	<10	92	<10	192	5
84137	<0.2	2.02	20	28	0.8	<5	2.42	2	19	26	64	4.57	1	0.07	<10	1.48	1557	11	0.03	3	0.103	13	0.57	<5	4	74	<5	0.16	<10	<10	87	<10	153	6
84138	<0.2	1.11	8	14	0.6	<5	3.62	1	10	113	13	1.18	<1	0.02	<10	0.16	399	9	0.01	3	0.064	6	0.04	<5	2	415	<5	0.12	<10	<10	39	<10	26	3
84139	<0.2	2.16	<5	31	0.8	<5	2.14	1	20	24	89	4.30	1	0.10	<10	1.46	1260	22	0.04	2	0.112	6	0.06	<5	4	109	<5	0.18	<10	<10	92	<10	142	5
84140	0.7	2.21	16	58	1.1	<5	2.53	2	19	38	280	4.25	1	0.24	<10	1.39	1447	20	0.03	4	0.108	8	0.32	<5	5	79	<5	0.20	<10	<10	94	<10	155	4
84141	0.6	1.76	11	44	0.9	<5	2.45	1	17	22	147	3.80	<1	0.15	<10	1.00	1176	5	0.03	4	0.106	5	0.24	<5	3	81	<5	0.17	<10	<10	77	<10	107	5
84142	<0.2	1.60	11	52	0.8	<5	5.29	1	18	26	64	4.30	1	0.14	<10	0.99	1624	8	0.03	2	0.098	10	0.93	<5	4	57	<5	0.15	<10	<10	85	<10	117	5

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2508RJ

Date : Jul-30-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/PO#shipment9

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84143	<0.2	1.78	<5	44	0.9	<5	3.27	1	18	22	49	3.78	<1	0.18	<10	0.98	1369	7	0.03	2	0.103	2	0.12	<5	4	70	<5	0.18	<10	<10	78	<10	116	4
84144	0.5	2.01	39	46	0.8	<5	3.25	2	19	19	122	4.67	1	0.19	<10	1.24	1679	9	0.02	2	0.104	7	0.82	<5	4	65	<5	0.16	<10	<10	89	<10	136	4
84145	0.2	1.96	6	43	0.9	<5	2.47	2	18	16	154	4.51	1	0.12	<10	1.16	1378	12	0.03	2	0.107	5	0.37	<5	4	68	<5	0.17	<10	<10	99	<10	157	5
84146	<0.2	2.27	<5	36	0.8	<5	2.67	2	20	22	140	4.99	<1	0.08	<10	1.60	1438	7	0.04	2	0.110	4	0.24	<5	4	81	<5	0.16	<10	<10	98	<10	227	6
84147	1.5	2.08	11	44	0.8	<5	4.03	2	19	19	393	4.83	<1	0.12	<10	1.30	1548	15	0.03	2	0.098	4	0.53	<5	4	71	<5	0.16	<10	<10	97	<10	230	5
84148	1.8	2.13	8	44	0.9	<5	2.60	2	19	25	509	4.38	1	0.18	<10	1.34	1356	24	0.03	2	0.104	6	0.30	<5	5	76	<5	0.19	<10	<10	97	<10	259	4
84149	1.0	2.13	18	50	0.9	<5	2.36	2	20	19	222	4.64	1	0.18	<10	1.33	1176	33	0.03	2	0.110	6	0.57	<5	5	67	<5	0.19	<10	<10	98	<10	251	4
84150	1.6	2.68	22	31	1.0	<5	3.05	3	21	24	477	5.19	<1	0.13	<10	1.64	1655	13	0.02	2	0.111	10	0.38	<5	5	51	<5	0.19	<10	<10	91	<10	268	5
84151	3.8	1.51	104	28	0.8	<5	3.82	3	19	40	591	3.84	<1	0.10	<10	0.87	1139	34	0.01	2	0.079	8	1.25	<5	2	94	<5	0.14	<10	<10	48	<10	251	4
84152	1.0	2.13	53	47	1.0	<5	4.38	2	23	20	194	4.96	1	0.18	<10	1.25	1795	5	0.02	2	0.114	10	0.83	<5	5	97	<5	0.22	<10	<10	86	<10	215	5
84153	6.0	1.98	65	52	0.9	<5	3.36	23	19	19	321	5.04	<1	0.21	<10	1.19	1954	5	0.02	2	0.098	2931	1.48	<5	5	48	<5	0.15	<10	<10	86	<10	2952	4
84154	3.6	1.41	49	39	0.7	<5	3.89	2	15	33	452	3.46	<1	0.21	<10	0.76	1361	15	0.01	2	0.079	38	0.82	<5	4	58	<5	0.11	<10	<10	64	<10	206	3
84155	>200.0	0.82	1655	86	<0.5	54	4.15	2	55	20	2263	2.89	2	0.08	10	0.23	817	122	0.05	22	0.078	355	0.58	308	1	134	<5	0.04	<10	<10	22	15	281	7
84156	1.7	1.84	38	41	0.9	<5	3.95	2	17	13	322	4.15	<1	0.19	<10	1.13	1572	20	0.02	2	0.103	17	0.55	<5	4	69	<5	0.14	<10	<10	80	<10	208	5
84157	1.1	1.86	57	39	0.8	<5	2.82	2	19	25	298	3.87	1	0.20	<10	1.17	1272	37	0.02	3	0.099	13	0.68	<5	4	66	<5	0.16	<10	<10	75	<10	212	4
84158	1.7	2.03	30	49	0.9	<5	3.26	2	18	20	405	4.06	<1	0.18	<10	1.35	1175	15	0.02	3	0.100	31	0.32	<5	6	65	<5	0.18	<10	<10	97	<10	234	6
84159	1.9	1.94	16	29	0.7	<5	1.52	2	17	38	371	4.24	<1	0.10	<10	1.17	952	69	0.02	2	0.088	23	0.25	<5	4	87	<5	0.15	<10	<10	77	<10	212	3
84160	1.0	2.20	16	69	1.0	<5	2.98	2	20	18	353	4.24	<1	0.22	<10	1.43	1306	26	0.03	1	0.114	8	0.35	<5	5	109	<5	0.20	<10	<10	98	<10	229	5
84161	2.6	1.73	103	76	0.9	<5	4.01	3	21	13	207	4.54	<1	0.35	<10	0.98	1676	19	0.01	1	0.132	15	1.89	<5	4	86	<5	0.16	<10	<10	59	<10	280	3
84162	1.9	0.50	132	46	<0.5	<5	7.71	7	10	68	59	2.34	<1	0.23	<10	0.21	1664	18	0.01	1	0.056	222	2.20	<5	2	293	<5	0.06	<10	<10	14	<10	718	1
84163	2.1	1.96	17	64	1.0	<5	4.45	2	20	8	270	4.25	<1	0.21	<10	1.21	1659	19	0.02	1	0.134	12	0.27	<5	5	114	<5	0.16	<10	<10	87	<10	279	5
84164	3.2	2.07	29	73	0.9	<5	2.49	2	22	12	351	4.88	<1	0.27	<10	1.26	1723	24	0.01	1	0.140	16	0.65	<5	4	54	<5	0.15	<10	<10	73	<10	379	3
84165	6.0	0.58	507	46	<0.5	<5	5.57	13	14	105	171	3.65	<1	0.19	<10	0.24	1083	30	0.01	2	0.062	65	3.37	<5	2	219	<5	0.07	<10	<10	17	<10	626	2
84166	2.5	2.12	22	54	1.0	<5	4.43	1	22	12	302	4.74	<1	0.16	<10	1.43	1901	42	0.02	<1	0.126	10	0.47	<5	5	102	<5	0.18	<10	<10	95	<10	284	4
84167	1.4	2.02	14	50	0.9	<5	4.48	1	15	25	157	3.35	<1	0.10	<10	1.27	1357	79	0.02	<1	0.120	6	0.12	<5	3	93	<5	0.14	<10	<10	66	<10	192	10
84168	1.4	1.78	15	52	1.0	<5	4.23	1	19	10	156	3.97	<1	0.16	<10	1.15	1537	62	0.02	<1	0.127	11	0.33	<5	4	87	<5	0.16	<10	<10	87	<10	179	4
84169	2.4	1.80	29	53	0.8	<5	4.28	1	20	11	224	4.40	<1	0.22	<10	1.06	1704	25	0.01	1	0.131	11	0.66	<5	4	77	<5	0.12	<10	<10	70	<10	251	3
84170	1.9	1.56	122	50	0.7	<5	4.30	3	19	11	121	4.54	<1	0.23	<10	0.83	1695	25	0.02	<1	0.128	36	1.50	<5	4	62	<5	0.11	<10	<10	68	<10	252	3
84171	1.5	2.03	25	47	0.8	<5	4.29	1	22	8	134	4.85	<1	0.21	<10	1.26	1596	30	0.02	1	0.141	10	0.44	<5	4	66	<5	0.13	<10	<10	82	<10	255	3
84172	1.8	2.11	20	50	0.8	<5	3.15	1	22	12	139	4.89	<1	0.21	<10	1.28	1269	60	0.02	<1	0.135	15	0.51	<5	4	65	<5	0.13	<10	<10	80	<10	273	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2508RJ

Date : Jul-30-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/PO#shipment9

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84173	3.0	1.71	17	46	0.6	<5	5.42	1	19	12	388	4.16	<1	0.17	<10	1.02	1625	79	0.02	1	0.129	11	0.50	<5	4	85	<5	0.11	<10	<10	70	<10	210	3
84174	1.6	1.76	<5	117	<0.5	<5	5.08	1	17	10	344	4.12	<1	0.16	<10	1.05	1666	48	0.02	<1	0.126	6	0.22	<5	4	189	<5	0.05	<10	<10	71	<10	252	3
84175	2.2	1.86	6	58	<0.5	<5	5.52	1	17	13	411	4.22	<1	0.18	<10	1.15	1740	57	0.02	<1	0.126	12	0.29	<5	4	106	<5	0.05	<10	<10	72	<10	253	2
84176	1.2	1.97	<5	72	0.8	<5	3.71	1	21	9	164	4.52	<1	0.19	<10	1.26	1352	47	0.02	1	0.138	10	0.25	<5	5	102	<5	0.14	<10	<10	87	<10	313	3
84177	2.4	2.07	46	63	0.9	<5	3.91	2	21	7	319	4.91	<1	0.22	<10	1.31	1368	50	0.02	<1	0.136	13	0.86	<5	5	66	<5	0.16	<10	<10	87	<10	317	3
84178	2.7	2.01	32	68	0.8	<5	3.91	2	21	6	301	4.90	<1	0.24	<10	1.22	1585	62	0.02	<1	0.140	10	0.92	<5	4	94	<5	0.14	<10	<10	73	<10	345	3
84179	4.2	1.93	1000	62	0.6	<5	4.34	19	19	6	398	4.78	<1	0.22	<10	1.22	1721	92	0.02	<1	0.137	14	0.90	<5	3	91	<5	0.09	<10	<10	74	<10	328	3
84180	0.2	0.90	<5	236	0.7	<5	0.49	<1	8	61	3	2.03	<1	0.47	<10	0.58	565	<2	0.05	4	0.076	3	0.01	<5	2	40	<5	0.13	<10	<10	38	<10	56	2
84181	1.4	2.10	41	65	0.6	<5	4.63	1	20	12	175	4.94	<1	0.21	<10	1.32	1613	137	0.02	<1	0.138	11	0.58	<5	4	95	<5	0.10	<10	<10	81	<10	256	3
84182	1.6	2.04	42	71	0.7	<5	4.94	1	20	6	166	4.87	<1	0.22	<10	1.32	1714	168	0.02	<1	0.131	9	0.65	<5	4	94	<5	0.10	<10	<10	78	<10	242	2
84183	2.2	1.59	171	66	<0.5	<5	5.36	4	17	10	169	4.13	<1	0.26	<10	0.89	1533	87	0.01	<1	0.123	17	1.36	<5	2	165	<5	0.01	<10	<10	48	<10	236	2
84184	4.3	1.97	164	75	<0.5	<5	5.08	4	19	6	380	5.11	<1	0.27	<10	1.08	1772	138	0.01	<1	0.130	26	1.18	<5	3	167	<5	0.01	<10	<10	57	<10	340	2
84185	5.8	1.81	139	78	<0.5	<5	4.14	4	19	16	586	4.90	<1	0.32	<10	0.92	1516	136	0.02	<1	0.131	21	1.80	<5	3	112	<5	0.02	<10	<10	61	<10	280	3
84186	3.9	1.74	134	103	0.8	<5	5.18	4	19	16	546	4.39	<1	0.42	<10	0.82	1679	99	0.02	1	0.139	12	1.54	<5	4	140	<5	0.10	<10	<10	59	<10	288	2
84187	2.1	2.10	20	80	0.9	<5	4.43	1	21	10	345	4.81	<1	0.28	<10	1.16	1718	55	0.02	<1	0.134	11	0.58	<5	5	120	<5	0.14	<10	<10	79	<10	272	3
84188	2.0	1.92	36	110	0.8	<5	6.59	1	19	10	341	4.27	<1	0.31	<10	1.05	1966	142	0.02	<1	0.129	14	0.72	<5	5	266	<5	0.12	<10	<10	75	<10	246	3
84189	3.3	2.16	30	139	0.6	<5	5.85	2	19	21	528	4.48	<1	0.25	<10	1.32	2169	103	0.01	1	0.114	11	0.49	<5	4	151	<5	0.07	<10	<10	68	10	362	3
84190	5.3	1.80	47	111	0.7	<5	7.42	3	17	17	711	4.22	<1	0.26	<10	1.04	2346	171	0.01	<1	0.106	17	0.98	<5	4	166	<5	0.07	<10	<10	53	15	369	3
84191	2.0	2.10	20	128	0.7	<5	3.22	2	19	7	494	4.96	<1	0.35	<10	1.06	1592	87	0.01	<1	0.149	11	0.58	<5	4	75	<5	0.07	<10	<10	67	<10	376	3
84192	3.9	2.04	32	100	0.5	<5	3.98	2	18	8	589	5.11	<1	0.33	<10	1.07	1783	119	0.01	<1	0.138	10	1.00	<5	4	99	<5	0.03	<10	<10	66	<10	352	2
84193	5.2	1.17	163	87	<0.5	<5	10.26	5	11	14	178	3.49	<1	0.26	<10	0.62	3271	53	0.01	<1	0.092	592	1.71	<5	2	223	<5	<0.01	<10	<10	31	<10	360	1
84194	1.3	0.67	243	101	<0.5	<5	12.89	8	8	27	38	2.69	<1	0.15	<10	0.42	3851	19	0.01	1	0.046	269	2.01	<5	2	253	<5	<0.01	<10	<10	16	<10	457	1
84195	3.3	1.77	180	134	0.5	<5	4.11	5	20	13	328	4.64	<1	0.32	<10	1.03	2427	57	0.01	1	0.139	79	1.71	<5	3	109	<5	0.05	<10	<10	59	<10	379	2
84196	2.1	1.77	204	85	<0.5	<5	5.12	5	17	17	276	4.81	<1	0.18	<10	1.16	2926	38	0.01	<1	0.113	212	1.62	<5	3	105	<5	0.08	<10	<10	67	<10	384	2
84197	1.5	2.30	92	120	0.6	<5	2.03	3	22	10	122	5.66	<1	0.22	<10	1.55	2527	24	0.01	<1	0.138	173	1.24	<5	4	55	<5	0.13	<10	<10	99	12	461	3
84198	1.3	2.30	90	121	0.5	<5	3.12	6	17	11	97	5.64	<1	0.20	<10	1.71	2958	22	0.01	<1	0.127	138	1.37	<5	5	71	<5	0.11	<10	<10	96	16	834	3
84199	1.4	1.22	247	62	<0.5	<5	8.59	6	10	29	75	3.81	<1	0.14	<10	0.92	3444	62	0.01	1	0.069	159	2.12	<5	2	166	<5	0.03	<10	<10	40	<10	329	2
84200	>200.0	0.85	1957	94	<0.5	52	4.40	39	64	22	2297	2.97	1	0.09	<10	0.24	862	133	0.05	23	0.090	410	0.70	316	2	149	<5	0.04	<10	<10	21	20	300	7
84201	1.2	1.51	259	66	<0.5	<5	4.68	6	13	28	30	4.56	<1	0.17	<10	1.20	2970	16	0.01	1	0.079	50	2.68	<5	2	105	<5	0.06	<10	<10	44	<10	364	2
84202	3.5	0.86	264	55	<0.5	<5	4.67	20	13	51	109	4.76	<1	0.13	<10	0.63	2511	9	0.01	1	0.065	1452	4.79	<5	2	122	<5	0.05	<10	<10	27	24	1885	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2508RJ

Date : Jul-30-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/PO#shipment9

Attention : Sue Deane

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84203	4.0	1.19	261	32	<0.5	5	10.34	82	11	37	102	7.17	<1	0.06	<10	1.05	3157	4	0.01	<1	0.052	2821	9.23	<5	2	156	<5	0.03	<10	<10	38	120	9338	3
84204	3.5	1.10	258	18	<0.5	8	15.06	94	11	45	73	8.31	<1	0.02	<10	0.98	3406	<2	0.01	<1	0.034	3064	>10.00	<5	2	180	<5	0.01	<10	<10	33	133	>10000	4
84205	7.2	0.46	284	17	<0.5	9	21.69	95	6	35	121	6.64	<1	0.02	10	0.45	4172	<2	0.01	<1	0.022	5172	>10.00	<5	1	291	<5	<0.01	<10	<10	12	137	>10000	3
84206	9.4	1.63	301	29	<0.5	5	1.92	94	11	47	80	10.31	<1	0.07	<10	1.47	2414	3	0.01	<1	0.064	4284	>10.00	<5	2	39	<5	0.04	<10	<10	53	144	>10000	4
84207	1.6	1.46	208	67	<0.5	<5	8.45	8	13	24	93	5.52	<1	0.13	<10	0.97	3436	4	0.01	2	0.094	292	3.67	<5	3	161	<5	0.05	<10	<10	69	<10	584	2
84208	10.8	1.14	111	91	<0.5	<5	5.13	53	14	39	540	4.32	<1	0.19	<10	0.62	2167	31	0.01	2	0.115	5414	3.05	<5	3	126	<5	0.07	<10	<10	55	75	6343	3
84209	5.4	1.31	202	68	<0.5	<5	8.90	24	11	28	179	5.33	1	0.15	<10	0.74	3478	7	0.01	4	0.067	943	2.77	5	2	255	<5	0.04	<10	<10	48	<10	3209	3
84210	1.2	0.70	166	77	<0.5	<5	11.93	11	5	30	76	2.68	1	0.13	11	0.36	4417	12	0.01	2	0.042	332	1.34	<5	1	171	<5	0.02	<10	<10	21	<10	1420	2
84211	0.7	0.76	145	103	<0.5	<5	3.58	1	5	59	39	2.30	<1	0.25	<10	0.30	1724	9	0.01	2	0.062	102	0.95	<5	1	76	<5	0.02	<10	<10	22	<10	115	2
84212	1.0	0.71	180	91	<0.5	<5	5.24	2	5	51	60	2.45	<1	0.16	<10	0.34	2373	8	0.01	2	0.048	193	1.09	<5	2	111	<5	0.02	<10	<10	30	<10	244	2
84213	0.5	0.67	50	112	<0.5	<5	6.47	1	5	46	50	1.44	1	0.31	10	0.21	2236	6	0.01	2	0.075	32	0.46	<5	1	171	<5	0.02	<10	<10	14	<10	137	2
84214	2.4	1.13	111	96	<0.5	<5	4.02	6	12	39	180	3.58	1	0.30	<10	0.43	1931	8	0.01	4	0.089	178	1.31	<5	3	89	<5	0.04	<10	<10	44	<10	718	3
84215	1.4	0.91	174	78	<0.5	<5	5.02	2	8	36	132	3.08	<1	0.28	<10	0.34	2227	43	0.01	2	0.066	68	1.48	<5	1	110	<5	0.03	<10	<10	22	<10	133	2
84216	1.7	1.09	95	85	<0.5	<5	4.46	5	9	34	145	3.29	<1	0.32	10	0.38	1907	13	0.01	2	0.075	101	1.14	<5	1	94	<5	0.04	<10	<10	29	<10	483	3
84217	3.0	0.88	180	77	<0.5	<5	4.62	4	7	38	248	3.16	<1	0.25	<10	0.35	1888	15	0.01	1	0.067	103	1.53	<5	1	111	<5	0.01	<10	<10	25	<10	347	2
84218	<0.2	0.65	41	52	<0.5	<5	18.83	1	5	16	87	1.87	1	0.21	14	0.23	5339	7	0.01	1	0.044	35	0.54	<5	1	233	5	0.02	<10	<10	17	<10	127	1
84219	1.4	1.59	24	89	0.5	<5	3.58	2	11	15	156	4.18	<1	0.29	<10	0.67	1997	11	0.01	3	0.118	6	0.38	<5	3	93	<5	0.06	<10	<10	67	<10	192	3
84220	0.6	1.43	43	84	<0.5	<5	7.43	3	11	13	109	3.82	<1	0.27	12	0.59	3201	9	0.01	2	0.109	90	0.47	<5	3	139	<5	0.03	<10	<10	65	<10	278	2
84221	0.6	1.41	38	102	0.5	<5	5.55	2	12	17	269	3.56	<1	0.32	11	0.60	2577	7	0.01	2	0.113	9	0.56	<5	3	117	<5	0.06	<10	<10	58	<10	173	3
84222	6.1	0.76	199	36	<0.5	<5	16.81	17	7	19	386	3.43	<1	0.13	12	0.45	5214	8	0.01	2	0.036	1567	2.26	<5	1	174	<5	0.02	<10	<10	25	<10	1794	2
84223	8.7	1.28	115	92	<0.5	<5	6.67	47	13	19	468	4.78	1	0.24	<10	0.67	2923	21	0.01	3	0.080	1405	2.73	<5	2	116	<5	0.03	<10	<10	47	<10	4903	3
84224	1.4	1.62	67	142	0.6	<5	2.71	5	13	14	149	4.06	1	0.36	<10	0.73	1769	22	0.01	3	0.117	48	0.81	<5	3	85	<5	0.08	<10	<10	53	<10	523	3
84225	<0.2	0.94	<5	213	0.5	<5	0.50	1	7	88	<1	1.89	<1	0.47	<10	0.56	529	<2	0.06	5	0.063	5	0.01	<5	2	57	<5	0.12	<10	<10	37	<10	62	2
84226	3.5	1.67	130	108	<0.5	<5	2.62	16	15	26	175	5.30	<1	0.30	<10	0.85	1822	24	0.01	4	0.105	428	2.04	<5	3	80	<5	0.05	<10	<10	62	<10	1750	3
84227	8.5	1.90	109	85	<0.5	<5	4.51	79	15	20	314	6.11	1	0.21	<10	1.10	2561	11	0.01	5	0.098	806	2.55	6	3	109	<5	0.04	<10	<10	70	<10	8855	4
84228	4.7	1.40	99	94	<0.5	<5	3.97	39	10	24	120	4.29	1	0.28	<10	0.71	2142	12	0.01	3	0.094	1486	1.76	<5	2	96	<5	0.03	<10	<10	47	<10	4334	3
84229	3.5	2.40	116	104	0.5	<5	5.11	5	21	21	226	7.32	1	0.35	<10	1.24	3047	47	0.01	4	0.126	347	1.98	5	3	106	<5	0.05	<10	<10	83	<10	530	4
84230	2.1	1.53	109	102	<0.5	<5	4.54	3	12	20	156	4.15	<1	0.30	<10	0.69	2236	29	0.01	3	0.106	128	0.80	<5	2	107	<5	0.04	<10	<10	50	<10	270	3
84231	1.2	1.50	41	109	0.5	<5	3.71	2	12	10	119	3.54	<1	0.34	12	0.68	1878	17	0.01	3	0.115	76	0.33	<5	3	110	<5	0.03	<10	<10	44	<10	239	2
84232	1.3	1.69	68	134	<0.5	<5	2.77	5	13	21	130	4.71	<1	0.32	10	0.94	1972	11	0.01	3	0.104	50	0.73	<5	3	80	<5	<0.01	<10	<10	53	<10	529	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2508RJ

Date : Jul-30-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/PO#shipment9

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Attention : Sue Deane

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84233	1.6	1.96	32	138	<0.5	<5	1.64	1	16	14	141	4.64	<1	0.36	<10	0.97	1397	18	0.01	2	0.135	13	0.83	<5	3	65	<5	0.01	<10	<10	54	<10	196	2
84234	2.7	1.98	43	97	<0.5	<5	3.67	15	12	28	213	5.33	<1	0.19	<10	0.92	1888	12	0.01	1	0.097	343	1.02	<5	4	112	<5	0.01	<10	<10	58	20	1738	2
84235	3.0	1.79	49	98	0.5	<5	2.33	3	16	9	254	4.48	<1	0.33	<10	0.86	1599	24	0.01	2	0.142	376	0.64	<5	3	66	<5	0.02	<10	<10	57	<10	426	2
SD08-04	3.3	0.90	50	21	<0.5	7	0.18	<1	67	30	23	11.31	<1	0.34	<10	0.15	245	1213	0.01	20	0.114	44	>10.00	<5	<1	4	<5	0.02	<10	<10	18	<10	116	6
139024	14.0	0.45	184	58	<0.5	<5	6.59	13	8	41	219	2.87	<1	0.14	<10	0.24	3129	8	0.01	2	0.059	1814	2.94	<5	1	116	<5	<0.01	<10	<10	19	24	2194	1
139025	27.6	0.25	278	76	<0.5	<5	3.18	20	10	112	239	4.25	<1	0.16	<10	0.06	2222	14	0.01	2	0.056	3501	4.02	<5	1	55	<5	<0.01	<10	<10	9	37	3302	2
139026	49.4	0.25	261	60	<0.5	<5	1.59	23	12	73	236	4.54	<1	0.15	<10	0.07	1421	8	0.01	2	0.070	4865	4.18	<5	1	31	<5	0.01	<10	<10	13	48	4278	2
139027	17.6	0.20	199	54	<0.5	<5	1.66	15	6	120	312	3.05	<1	0.13	<10	0.06	1749	5	<0.01	2	0.035	3313	3.06	<5	<1	25	<5	<0.01	<10	<10	7	29	2734	1
139028	15.4	0.16	137	60	<0.5	<5	0.74	13	5	116	252	2.10	<1	0.10	<10	0.04	2302	4	0.01	3	0.026	2680	1.29	<5	<1	9	<5	<0.01	<10	<10	4	23	2211	1
139029	17.2	0.25	210	62	<0.5	<5	1.80	13	6	117	331	2.46	<1	0.16	<10	0.05	1932	9	<0.01	2	0.042	2781	1.98	<5	1	27	<5	<0.01	<10	<10	5	22	2028	1
139030	10.8	0.33	405	118	<0.5	<5	0.10	7	7	78	129	4.65	<1	0.21	<10	0.05	566	29	0.01	1	0.104	485	1.55	<5	1	3	<5	<0.01	<10	<10	10	<10	287	2
139031	23.6	0.29	1800	56	<0.5	<5	0.11	33	7	77	98	5.21	<1	0.23	<10	0.05	294	18	0.01	<1	0.094	758	3.34	6	1	5	<5	<0.01	<10	<10	11	<10	277	2
139032	40.5	0.50	1122	84	<0.5	<5	0.31	22	8	65	124	4.11	<1	0.20	<10	0.19	840	8	0.01	2	0.082	626	2.38	6	1	6	<5	<0.01	<10	<10	16	<10	443	2
139033	26.6	0.79	2376	107	<0.5	<5	0.15	47	12	64	167	5.10	<1	0.19	<10	0.33	1598	11	0.01	1	0.093	430	1.85	11	1	3	<5	<0.01	<10	<10	22	<10	539	2
139034	16.5	0.47	369	79	<0.5	<5	5.32	19	9	76	164	2.93	<1	0.15	<10	0.23	3572	8	0.01	2	0.058	2080	2.34	<5	1	113	<5	<0.01	<10	10	19	29	2557	1
139035	115.6	0.77	507	88	<0.5	<5	3.51	14	10	66	76	3.69	<1	0.15	<10	0.48	2932	4	0.01	2	0.084	620	2.43	<5	2	49	<5	<0.01	<10	<10	31	<10	828	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2558-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment1-12bags**
Attn: **Sue Deane**

Aug-01-08

We hereby certify the following assay of 24 core samples submitted Jul-17-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84236	0.14	0.14	9.3
84237	0.07		5.9
84238	0.32		4.1
84239	0.48		4.6
84240	0.09		2.4
84241	0.32		5.9
84242	0.23		10.6
84243	0.08		4.5
84244	0.22		16.9
84245	0.35	0.36	5.5
84246	0.47		5.8
84247	0.21		4.4
84248	0.28		6.0
84249	0.19		2.4
84250	0.39		4.9
84251	0.36		4.4
84252	0.15		1.9
84253	0.17		9.9
84254	0.25		6.3
84255	0.17	0.15	8.1
84256	<0.01		<0.1
84257	0.20		5.1
84258	0.29		12.5
84259	0.28		4.5
*0218	0.92		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2558-RA2

Company: **Ascot Resources Ltd**
 Project: **Dilworth/Shipment1-12bags**
 Attn: **Sue Deane**

Aug-01-08

We hereby certify the following assay of 24 core samples submitted Jul-17-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne	Zn %
84260	0.44	0.41	7.0		
84261	0.27		4.1		
84262	0.21		3.1		
84263	0.13		6.1		
84264	0.87		5.2		
84265	0.40		10.3		
84266	0.59		12.9		
84267	0.74		15.2		
84268	0.45		8.3		
84269	0.32	0.32	4.7		
84270	0.24		2.7		
84271	0.39		1.5		
84272	0.51		7.2		
84273	0.96		36.8		
84274	0.18		6.1		
84275	0.24		2.6		
84276	0.37		5.7		
84277	1.39		>200	218.1	
84278	0.30		7.0		
84279	0.56	0.49	32.3		
84280	5.86		>200	2531	1.61
84281	0.13		8.1		
84282	0.38		15.0		
84283	0.53		4.3		
*0218	0.89				
*CCu-1c				130.5	3.96
*BLANK	<0.01			<0.1	<0.01

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2558-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment1-12bags**
Attn: **Sue Deane**

Aug-01-08

We hereby certify the following assay of 24 core samples
submitted Jul-17-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84284	0.12	0.12	3.3
84285	0.32		3.3
84286	0.43		6.6
84287	0.12		1.2
84288	0.08		0.4
84289	0.06		0.5
84290	0.13		1.4
84291	0.08		4.4
84292	0.07		1.1
84293	0.11	0.11	3.1
84294	0.14		3.0
84295	0.09		3.5
84296	0.40		6.1
84297	1.44		12.2
84298	1.52		17.5
84299	0.08		8.2
84300	0.03		<0.1
84301	0.12		5.5
84302	0.68		115
84303	0.13	0.11	2.1
84304	0.33		38.1
84305	0.19		27.5
84306	0.24		11.5
84307	0.20		2.3
*0218	0.93		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2558-RA4

Company: **Ascot Resources Ltd**
 Project: **Dilworth/Shipment1-12bags**
 Attn: **Sue Deane**

Aug-01-08

We hereby certify the following assay of 24 core samples submitted Jul-17-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
84308	0.11	0.08	2.6	
84309	0.40		13.5	
84310	0.64		21.5	
84311	0.12		2.1	
84312	0.22		2.7	
84313	0.11		1.9	
84314	0.31		2.5	
84315	0.35		2.6	
84316	0.12		2.4	
84317	0.08	0.06	1.4	
84318	0.16		1.7	
84319	0.05		3.0	
84320	0.06		1.6	
84321	0.01		1.7	
84322	0.03		0.6	
84323	<0.01		1.1	
84324	0.01		1.0	
84325	1.39		>200	221.1
84326	0.02		1.9	
84327	0.01	0.01	4.3	
84328	0.01		0.7	
84329	0.03		2.0	
84330	0.17		3.5	
84331	0.58		6.8	
*0218	0.90			
*CCu-1c				130.2
*BLANK	<0.01			<0.1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2558-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment1-12bags**
Attn: **Sue Deane**

Aug-01-08

We hereby certify the following assay of 24 core samples submitted Jul-17-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84332	0.10	0.09	1.2
84333	0.06		2.0
84334	0.09		1.5
84335	0.13		2.3
84336	0.03		0.4
84337	0.06		0.8
84338	0.06		0.6
84339	0.07		0.8
84340	0.15		1.3
84341	1.96	1.96	10.2
84342	0.31		3.7
84343	0.69		9.3
84344	0.07		4.2
84345	0.15		1.1
84346	0.09		2.0
84347	0.14		2.0
84348	0.18		2.5
84349	0.10		2.0
84350	0.01		<0.1
84351	0.03	0.02	1.8
84352	0.37		3.2
84353	0.27		55.1
84354	0.03		1.5
84355	0.45		3.8
*0218	0.90		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2558-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment1-12bags**
Attn: **Sue Deane**

Aug-01-08

We hereby certify the following assay of 24 core samples submitted Jul-17-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84356	0.29	0.25	10.4
84357	0.98		100
84358	0.74		5.7
84359	0.36		5.6
84360	0.20		2.6
84361	0.38		0.6
84362	0.11		1.2
84363	0.34		3.2
84364	0.44		6.6
84365	0.58	0.52	4.4
84366	0.15		2.3
84367	0.20		2.1
84368	0.07		2.4
84369	0.22		2.4
84370	0.12		2.3
84371	2.89		32.8
84372	2.72		22.1
139036	1.69		10.3
139037	1.93		12.3
139038	1.13	0.74	5.2
139039	0.90		6.5
139040	2.02		14.2
139041	2.13		14.6
139042	1.31		15.8
*0218	0.90		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2558-RA7

Company: **Ascot Resources Ltd**
 Project: **Dilworth/Shipment1-12bags**
 Attn: **Sue Deane**

Aug-01-08

We hereby certify the following assay of 24 core & chip samples submitted Jul-17-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %	Zn %
139043	0.71	0.58	6.4		
139044	1.70		40.9		
139045	0.74		5.5		
139046	1.62		3.1		
139047	0.07		1.2		
139048	0.28		22.8		
139049	0.73		12.9		
139050	0.15		1.3		
139051	0.09		12.7		
139052	0.32	0.24	60.6		
139053	0.28		20.3		
139054	0.14		11.1		
139055	0.43		9.5		
139056	0.18		8.1		
139057	0.20		8.9		
139058	0.23		6.4		
139059	0.10		1.5		
139060	1.33		56.5	2.71	0.95
139061	0.36		25.9	1.42	1.52
139062	0.24	0.18	18.7	1.07	1.00
139063	0.20		9.2		
SD0805	0.09		21.4		
SD0806	0.20		11.6		
*0218	0.92				
*CCu-1c				0.36	3.96
*BLANK	<0.01			<0.01	<0.01

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2558-RA8

Company: **Ascot Resources Ltd**
Project: Dilworth/Shipment1-12bags
Attn: Sue Deane

Aug-01-08

We *hereby certify* the following assay of 4 core samples
submitted Jul-17-08

**Sample
Name**

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2558RJ

Date : Aug-01-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipments1-12bags

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84236	9.3	2.33	330	155	<0.5	<5	1.02	4	34	40	123	9.31	<1	0.48	11	1.20	2389	4	0.01	5	1822	168	4.84	23	4	59	<5	0.01	<10	28	102	<10	224	5
84237	5.9	3.64	180	278	0.5	<5	4.52	6	43	55	73	10.88	<1	0.63	12	2.06	4742	3	0.02	8	2174	55	3.36	17	7	184	<5	0.01	<10	43	152	<10	397	6
84238	4.1	1.90	161	142	<0.5	<5	1.28	3	27	20	46	6.39	<1	0.39	<10	0.82	2291	2	0.01	4	1440	65	2.51	8	4	66	<5	0.01	<10	18	83	<10	166	4
84239	4.6	2.11	106	175	<0.5	<5	1.16	5	21	35	172	5.88	<1	0.41	<10	1.04	2534	<2	0.01	6	1242	120	1.64	6	4	71	<5	0.01	<10	16	77	<10	458	3
84240	2.4	2.27	98	132	<0.5	<5	0.61	2	23	16	70	5.98	<1	0.30	<10	1.24	2486	<2	0.02	6	1351	26	1.22	5	4	55	<5	0.01	<10	20	69	<10	109	3
84241	5.9	2.05	140	179	<0.5	<5	0.73	3	23	21	202	5.69	<1	0.37	10	1.01	2635	<2	0.01	7	1205	48	1.32	7	3	99	<5	0.01	<10	18	69	<10	150	3
84242	10.6	2.22	157	167	<0.5	<5	0.51	3	22	14	104	6.09	<1	0.36	11	1.22	2102	<2	0.01	8	1038	118	1.58	9	3	46	<5	0.01	<10	17	66	<10	221	3
84243	4.5	2.83	119	290	<0.5	<5	0.63	4	24	18	154	6.62	<1	0.39	<10	1.83	2312	2	0.01	6	1297	110	0.97	7	5	58	<5	<0.01	<10	21	101	<10	306	4
84244	16.9	1.82	375	131	<0.5	<5	1.98	34	20	22	165	5.70	<1	0.32	<10	1.12	2156	3	0.01	5	1043	180	1.85	9	3	109	<5	<0.01	<10	20	69	<10	3169	3
84245	5.5	1.98	228	128	<0.5	<5	1.58	6	21	40	82	6.85	<1	0.31	<10	1.21	2190	3	0.01	5	939	392	3.22	9	4	108	<5	0.01	<10	22	88	<10	438	4
84246	5.8	2.12	1085	117	<0.5	<5	0.59	42	22	34	125	7.27	<1	0.29	<10	1.40	1916	2	0.01	4	1065	417	3.39	9	4	45	<5	0.01	<10	20	103	<10	3636	4
84247	4.4	2.50	429	105	<0.5	<5	0.86	14	24	19	95	7.50	<1	0.24	<10	1.64	2309	3	0.01	6	1129	210	2.83	8	5	55	<5	0.01	<10	24	130	<10	1178	4
84248	6.0	1.54	154	114	<0.5	<5	1.71	3	18	64	179	4.95	<1	0.32	<10	0.75	2279	4	0.01	7	844	313	2.65	6	3	119	6	0.01	<10	12	43	<10	208	3
84249	2.4	1.62	107	116	<0.5	<5	1.76	2	19	23	53	5.37	<1	0.23	<10	1.05	2339	<2	0.01	4	939	115	2.56	<5	4	115	6	0.01	<10	12	83	<10	153	3
84250	4.9	2.24	179	117	<0.5	<5	1.06	3	22	26	103	6.34	<1	0.30	<10	1.57	2530	2	0.01	4	1015	234	2.69	5	4	37	5	0.01	<10	14	91	<10	257	4
84251	4.4	2.61	47	145	<0.5	<5	1.46	7	19	28	76	5.43	<1	0.28	<10	1.98	2823	<2	0.01	4	1142	948	0.90	5	6	55	<5	0.01	<10	14	124	<10	742	3
84252	1.9	2.86	39	133	<0.5	<5	1.97	4	23	11	99	6.41	<1	0.27	<10	2.00	3235	<2	0.01	4	1223	67	1.70	<5	6	85	5	0.01	<10	19	145	<10	268	4
84253	9.9	2.52	59	150	<0.5	<5	0.74	43	20	16	276	6.01	<1	0.28	<10	1.87	2517	<2	0.01	4	1097	862	1.90	9	4	26	5	0.01	<10	13	125	<10	4144	4
84254	6.3	1.69	156	115	<0.5	<5	2.03	8	16	29	42	5.81	<1	0.20	<10	1.21	2326	2	0.01	3	830	618	3.50	6	4	54	5	0.01	<10	14	115	<10	802	4
84255	8.1	1.41	156	136	<0.5	<5	0.90	3	20	71	46	5.07	<1	0.36	<10	0.71	1635	6	0.01	4	1052	1465	3.19	8	3	33	<5	<0.01	<10	<10	64	<10	243	3
84256	<0.2	1.07	<5	245	<0.5	<5	0.51	<1	6	108	<1	2.14	<1	0.53	<10	0.62	596	<2	0.07	6	707	8	<0.01	<5	2	44	10	0.13	21	<10	41	<10	54	2
84257	5.1	2.15	180	85	<0.5	5	1.30	4	21	28	19	7.45	<1	0.30	<10	1.31	3067	6	0.01	4	1045	189	>5.00	7	4	53	7	0.01	<10	23	86	<10	228	5
84258	12.5	1.99	182	99	<0.5	<5	0.68	6	23	29	19	7.35	<1	0.23	<10	1.33	3192	<2	0.01	4	1158	322	4.36	6	4	25	5	0.01	<10	21	91	<10	511	4
84259	4.5	0.97	205	106	<0.5	<5	2.13	5	18	100	21	5.67	<1	0.21	<10	0.56	2305	3	0.01	5	936	285	4.56	7	3	101	<5	0.01	<10	16	55	<10	389	3
84260	7.0	1.08	274	69	<0.5	<5	0.75	13	22	40	43	6.79	<1	0.22	<10	0.66	1391	3	0.01	4	919	609	>5.00	9	4	40	<5	0.01	<10	24	97	<10	812	4
84261	4.1	0.96	219	100	<0.5	<5	1.74	4	17	81	<1	5.75	<1	0.25	<10	0.60	2039	2	0.01	5	1008	288	4.15	7	3	166	<5	0.01	<10	24	58	<10	337	4
84262	3.1	0.24	79	123	<0.5	<5	1.13	10	6	96	<1	3.19	<1	0.20	<10	0.09	619	<2	0.01	3	288	342	2.61	<5	1	53	<5	<0.01	<10	12	12	<10	1311	2
84263	6.1	0.29	107	172	<0.5	<5	4.33	12	5	121	21	1.96	<1	0.20	<10	0.10	1957	<2	0.01	3	303	647	1.62	8	1	236	<5	<0.01	<10	17	13	<10	1521	2
84264	5.2	0.42	154	122	<0.5	<5	2.20	9	4	127	<1	2.82	<1	0.18	<10	0.26	1401	<2	0.01	4	326	435	1.55	9	1	102	<5	<0.01	<10	18	13	<10	1027	2
84265	10.3	0.30	395	67	<0.5	<5	1.12	14	6	122	6	5.24	<1	0.23	<10	0.11	658	5	0.01	3	382	1670	>5.00	11	1	73	<5	<0.01	<10	20	8	<10	2043	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2558RJ

Date : Aug-01-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment1-12bags

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84266	12.9	0.21	410	75	<0.5	<5	2.21	9	4	251	14	3.65	<1	0.15	<10	0.06	1230	5	0.01	7	254	707	3.51	18	1	168	<5	<0.01	<10	15	5	<10	1086	2
84267	15.2	0.59	602	47	<0.5	<5	1.09	12	7	130	5	8.11	1	0.20	<10	0.32	1088	2	0.02	4	463	889	>5.00	41	1	97	<5	<0.01	<10	32	17	<10	1278	5
84268	8.3	0.80	282	88	<0.5	<5	0.39	16	7	199	34	5.65	<1	0.18	<10	0.47	835	2	0.02	6	584	1204	4.24	15	1	27	<5	<0.01	<10	22	22	<10	1898	3
84269	4.7	1.02	401	86	<0.5	<5	3.00	16	11	78	<1	6.63	<1	0.22	<10	0.60	2295	<2	0.02	4	885	451	4.96	17	2	244	<5	<0.01	<10	28	25	<10	1594	4
84270	2.7	1.24	295	140	<0.5	<5	0.69	7	9	124	13	5.00	<1	0.24	<10	0.78	1514	2	0.01	5	945	189	1.90	7	2	48	<5	<0.01	<10	21	38	<10	737	3
84271	1.5	0.82	156	137	<0.5	<5	5.79	9	7	69	9	3.91	<1	0.24	<10	0.52	2177	<2	0.01	3	670	240	2.17	6	2	108	<5	<0.01	<10	19	27	<10	1026	2
84272	7.2	0.45	263	117	<0.5	<5	1.71	11	6	208	23	3.96	<1	0.20	<10	0.20	1293	3	0.01	6	450	794	2.71	11	1	148	<5	<0.01	<10	21	12	<10	1413	3
84273	36.8	0.56	415	46	<0.5	<5	0.97	89	17	116	369	6.90	<1	0.25	<10	0.23	857	4	0.01	4	625	2259	>5.00	33	1	61	<5	<0.01	<10	24	13	<10	9386	4
84274	6.0	0.66	205	113	<0.5	<5	3.43	12	9	>10000	42	4.28	<1	0.24	<10	0.28	1769	2	0.01	5	666	524	3.43	10	1	83	<5	0.01	<10	19	14	<10	1585	3
84275	2.6	1.00	204	114	<0.5	<5	0.54	5	11	78	<1	4.55	<1	0.29	<10	0.47	1178	2	0.01	4	926	306	2.85	6	1	21	<5	<0.01	<10	17	19	<10	545	3
84276	5.6	0.85	191	121	<0.5	<5	0.91	5	12	155	29	4.59	<1	0.34	<10	0.37	1233	3	0.01	7	912	369	3.40	16	2	65	<5	<0.01	<10	16	18	<10	499	3
84277	>200.0	0.90	1843	96	<0.5	60	4.69	2	59	21	2601	3.41	1	0.10	<10	0.24	950	128	0.06	23	833	402	0.62	417	2	140	<5	0.04	<10	<10	21	18	330	8
84278	7.0	0.86	270	102	<0.5	<5	0.97	6	10	76	22	4.60	<1	0.32	<10	0.35	1156	3	0.01	4	831	328	2.96	19	1	37	<5	<0.01	<10	18	20	<10	648	3
84279	32.3	1.08	297	123	<0.5	<5	0.80	7	10	109	37	5.09	<1	0.33	<10	0.58	1364	4	0.01	6	870	267	2.81	19	2	47	<5	<0.01	<10	22	36	<10	886	3
84280	>200.0	0.81	205	71	<0.5	<5	0.82	143	11	71	368	6.14	<1	0.32	<10	0.41	1004	<2	0.01	4	969	7545	>5.00	270	1	47	<5	<0.01	<10	26	27	<10	>10000	4
84281	8.1	0.77	134	100	<0.5	<5	0.36	5	10	86	50	4.94	<1	0.26	<10	0.38	779	<2	0.01	5	857	678	3.31	8	1	35	<5	<0.01	<10	18	23	<10	529	3
84282	15.0	1.22	128	136	<0.5	<5	0.54	7	11	55	56	4.56	<1	0.27	<10	0.78	1467	<2	0.01	4	1034	205	2.18	10	2	48	<5	<0.01	<10	20	42	<10	853	3
84283	4.3	1.43	145	144	<0.5	<5	0.91	4	10	89	52	5.06	<1	0.28	<10	0.96	1847	<2	0.02	6	962	147	2.21	6	2	76	<5	<0.01	<10	27	50	<10	359	3
84284	3.3	1.52	66	114	<0.5	<5	1.19	3	11	52	98	4.27	<1	0.27	<10	0.95	2034	<2	0.02	3	972	166	1.74	<5	2	99	6	>10.00	<10	<10	42	<10	261	3
84285	3.3	1.01	78	124	<0.5	<5	0.96	3	9	88	8	3.99	<1	0.25	<10	0.53	1384	<2	0.01	4	717	120	2.42	<5	1	68	5	>10.00	<10	<10	23	<10	220	3
84286	6.6	1.37	84	104	<0.5	<5	0.69	10	10	43	22	4.34	<1	0.24	<10	0.75	1710	<2	0.03	3	907	569	1.92	5	2	30	<5	>10.00	<10	<10	29	<10	1154	3
84287	1.2	1.35	51	110	<0.5	<5	1.37	4	11	43	17	4.49	<1	0.27	<10	0.77	2018	<2	0.02	3	894	198	2.02	<5	2	56	<5	>10.00	<10	<10	35	<10	432	3
84288	0.4	1.40	49	125	<0.5	<5	1.54	2	11	44	11	4.52	<1	0.24	<10	0.82	2061	2	0.02	3	874	47	2.02	<5	2	72	<5	>10.00	<10	<10	38	<10	119	3
84289	0.5	1.42	36	143	<0.5	<5	1.42	2	12	45	10	4.38	<1	0.30	<10	0.78	1984	<2	0.01	3	991	127	1.69	5	2	63	<5	>10.00	<10	<10	42	<10	173	3
84290	1.4	1.10	77	121	<0.5	<5	0.89	6	11	66	2	4.04	<1	0.22	<10	0.65	1414	<2	0.02	3	830	470	2.21	<5	2	43	<5	>10.00	<10	<10	30	<10	614	3
84291	4.4	1.36	57	85	<0.5	<5	1.85	5	10	42	3	4.33	<1	0.20	<10	0.80	1797	<2	0.03	3	856	390	1.77	6	2	67	<5	>10.00	<10	<10	33	<10	474	3
84292	1.1	1.36	67	89	<0.5	<5	1.07	4	10	52	1	4.43	<1	0.20	<10	0.83	1637	<2	0.03	3	890	413	2.14	5	2	43	<5	>10.00	<10	<10	32	<10	431	3
84293	3.1	1.17	146	90	<0.5	<5	2.69	4	10	33	<1	4.75	<1	0.22	<10	0.66	1898	<2	0.02	3	830	236	2.63	10	2	59	<5	>10.00	<10	<10	23	<10	437	3
84294	3.0	0.94	99	112	<0.5	<5	0.91	17	9	57	3	4.28	<1	0.23	<10	0.50	1218	2	0.02	3	771	1775	2.54	6	1	39	<5	>10.00	<10	<10	20	<10	2209	3
84295	3.5	1.79	129	161	<0.5	<5	0.30	4	21	39	84	5.28	<1	0.29	<10	0.91	2029	3	0.02	2	1160	70	1.54	9	4	2	6	>10.00	<10	<10	83	<10	225	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2558RJ

Date : Aug-01-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment1-12bags

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84296	6.1	1.87	226	109	<0.5	<5	1.12	4	28	24	87	5.97	<1	0.37	<10	0.85	2519	<2	0.01	3	1146	84	2.67	9	4	43	5	>10.00	<10	13	53	<10	266	3
84297	12.2	1.66	215	112	<0.5	<5	1.62	5	25	24	82	6.16	<1	0.33	<10	0.87	2713	<2	0.01	3	1122	421	2.99	7	4	65	<5	>10.00	<10	18	62	<10	500	3
84298	17.5	2.21	110	181	<0.5	<5	0.72	4	23	12	73	5.77	<1	0.28	<10	1.34	2714	<2	0.01	3	1231	319	1.30	6	4	41	<5	>10.00	<10	13	92	<10	368	3
84299	8.2	2.52	88	288	<0.5	<5	0.34	3	23	13	55	6.20	<1	0.32	11	1.43	2583	5	0.01	3	1325	59	1.02	8	5	10	<5	>10.00	<10	11	111	<10	291	4
84300	<0.2	1.13	<5	268	<0.5	<5	0.54	1	7	116	<1	2.38	<1	0.57	<10	0.69	662	2	0.07	6	702	11	0.02	<5	3	51	6	>10.00	<10	<10	44	<10	59	3
84301	5.5	1.96	146	145	<0.5	<5	1.41	2	19	24	44	5.20	<1	0.36	<10	1.10	2432	6	0.01	2	1135	140	1.33	7	4	47	<5	>10.00	<10	<10	85	<10	127	3
84302	115.2	0.45	705	99	<0.5	<5	3.41	10	12	112	67	4.09	<1	0.19	<10	0.19	1854	7	0.01	4	436	661	3.98	26	2	90	<5	>10.00	<10	10	24	<10	1196	2
84303	2.1	2.71	90	101	<0.5	<5	2.48	2	25	11	66	5.92	<1	0.30	<10	1.70	3181	<2	0.01	5	996	54	1.18	6	6	90	5	>10.00	<10	16	104	<10	112	4
84304	38.1	2.80	85	129	<0.5	<5	2.03	5	20	16	211	5.90	<1	0.20	<10	2.01	3311	3	0.01	4	973	395	1.10	10	6	49	5	>10.00	<10	17	158	<10	466	4
84305	27.5	2.73	219	131	<0.5	<5	1.47	6	20	14	167	5.94	<1	0.19	<10	1.96	2895	2	0.01	5	943	363	1.33	8	7	41	5	>10.00	<10	13	172	<10	550	4
84306	11.5	2.79	220	112	<0.5	<5	2.31	3	25	8	226	6.43	<1	0.14	<10	1.89	3286	<2	0.02	4	1134	61	1.33	6	8	81	5	>10.00	<10	17	224	<10	241	4
84307	2.3	2.62	124	138	<0.5	<5	2.08	3	24	5	98	6.64	<1	0.23	<10	1.84	2823	<2	0.01	5	1195	19	1.32	5	7	54	<5	>10.00	<10	17	208	<10	139	4
84308	2.6	2.57	93	153	<0.5	<5	1.65	3	20	24	87	6.39	<1	0.24	<10	1.92	2792	<2	0.01	5	1146	16	1.74	7	7	43	<5	0.01	<10	20	189	<10	174	4
84309	13.5	2.55	112	111	<0.5	<5	1.83	6	19	13	82	6.25	<1	0.19	<10	2.02	2772	<2	0.02	4	1112	170	1.63	6	7	54	<5	0.01	<10	20	185	<10	659	4
84310	21.5	2.16	131	91	<0.5	<5	3.10	40	17	21	246	6.48	<1	0.19	<10	1.64	2871	<2	0.01	4	950	1430	2.58	8	6	92	<5	0.01	<10	23	155	<10	4432	3
84311	2.1	2.77	47	123	<0.5	<5	4.17	3	21	8	108	6.64	<1	0.21	<10	2.14	3527	<2	0.02	5	1190	21	0.92	7	9	175	<5	0.01	<10	24	186	<10	118	4
84312	2.7	2.44	148	133	<0.5	<5	2.90	3	25	9	96	7.11	<1	0.28	<10	1.70	3225	<2	0.02	5	1243	34	1.65	7	7	130	<5	0.01	<10	28	151	<10	339	4
84313	1.9	2.83	60	126	<0.5	<5	2.10	2	23	15	51	6.75	<1	0.21	<10	2.16	3195	<2	0.02	5	1177	71	1.12	5	8	116	<5	0.01	<10	26	172	<10	90	4
84314	2.5	2.64	60	118	<0.5	<5	2.61	2	22	8	97	6.23	<1	0.22	<10	1.91	3594	<2	0.02	5	1061	7	1.04	<5	7	75	<5	0.01	<10	25	133	<10	82	3
84315	2.6	2.34	88	84	<0.5	<5	2.83	2	21	15	86	6.14	<1	0.13	<10	1.74	3277	<2	0.02	5	1003	12	1.52	5	8	100	<5	0.01	<10	24	162	<10	75	3
84316	2.4	2.66	114	88	<0.5	<5	3.10	2	22	2	116	6.83	<1	0.16	<10	1.86	3361	<2	0.03	4	1129	9	1.19	<5	8	119	<5	0.01	<10	27	174	<10	80	4
84317	1.4	2.40	123	110	<0.5	<5	4.78	2	21	8	68	6.25	<1	0.20	<10	1.69	3409	<2	0.02	4	1029	11	1.13	<5	6	117	<5	<0.01	<10	23	129	<10	81	3
84318	1.7	2.21	247	82	<0.5	<5	3.87	2	29	20	134	7.08	<1	0.35	<10	1.36	2389	<2	0.02	6	1121	19	3.99	<5	5	118	<5	0.02	<10	<10	100	<10	97	4
84319	3.0	1.65	127	122	<0.5	<5	4.67	3	29	12	231	6.90	<1	0.41	<10	1.03	1738	<2	0.01	5	1389	24	4.49	6	4	135	<5	0.09	<10	23	63	<10	101	4
84320	1.6	2.27	70	161	<0.5	<5	8.24	2	20	8	120	5.64	<1	0.42	<10	1.33	3022	<2	0.02	4	1016	10	1.86	5	5	228	<5	0.03	<10	22	93	<10	70	3
84321	1.7	2.75	35	148	<0.5	<5	3.49	2	30	12	144	6.40	<1	0.35	<10	1.78	2229	<2	0.02	6	1237	7	0.74	5	5	113	<5	0.03	<10	22	126	<10	91	3
84322	0.6	2.88	79	133	<0.5	<5	5.00	5	46	10	100	6.71	<1	0.32	<10	1.77	2643	<2	0.02	7	1187	12	1.52	<5	5	143	<5	0.03	<10	<10	201	<10	328	4
84323	1.1	2.55	46	153	<0.5	<5	6.49	2	34	11	109	5.90	<1	0.36	<10	1.35	2663	<2	0.02	5	1219	6	0.77	<5	5	244	<5	0.04	<10	24	129	<10	90	3
84324	1.0	2.59	42	207	<0.5	<5	5.14	2	27	3	117	6.58	<1	0.44	<10	1.34	2432	<2	0.02	6	1200	5	1.04	5	5	147	<5	0.02	<10	25	147	<10	97	3
84325	>200.0	1.31	1540	134	<0.5	50	4.79	2	52	78	2275	3.64	<1	0.25	11	0.28	1026	103	0.09	21	766	334	0.53	344	2	151	<5	0.06	<10	<10	31	14	293	9

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2558RJ

Date : Aug-01-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment1-12bags

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84326	1.9	2.27	59	143	<0.5	<5	4.06	2	31	1	145	6.43	<1	0.44	<10	1.08	2115	<2	0.01	6	971	11	0.74	6	4	99	<5	0.02	<10	21	136	<10	98	3
84327	4.3	2.20	225	164	<0.5	<5	2.98	4	30	5	171	5.31	<1	0.43	<10	0.99	1546	<2	0.01	7	1171	27	0.50	8	4	80	<5	0.01	<10	18	96	<10	249	3
84328	0.7	2.73	25	187	<0.5	<5	5.30	3	30	5	68	6.60	<1	0.47	<10	1.18	2281	<2	0.01	6	1193	25	0.45	<5	5	131	<5	0.02	<10	29	89	<10	104	4
84329	2.0	2.88	70	203	0.5	<5	3.22	3	37	3	84	7.51	<1	0.44	<10	1.22	2051	<2	0.01	4	1352	33	1.30	6	5	86	<5	0.02	<10	26	74	<10	113	4
84330	3.5	1.46	270	127	<0.5	<5	3.42	4	26	13	81	5.96	<1	0.46	<10	0.56	1330	<2	0.01	4	1189	56	3.77	7	4	91	<5	0.03	<10	17	46	<10	180	4
84331	6.8	0.77	655	72	<0.5	<5	3.55	10	28	46	64	6.68	<1	0.50	<10	0.19	1126	3	0.01	5	1337	631	>5.00	11	2	96	<5	0.07	<10	21	24	<10	1007	4
84332	1.2	0.90	219	126	<0.5	<5	5.05	2	13	19	23	4.08	<1	0.37	<10	0.35	1690	<2	0.01	1	1127	47	3.31	<5	2	153	<5	0.01	<10	<10	16	<10	129	3
84333	2.0	1.63	228	137	<0.5	<5	3.13	4	18	7	85	5.59	<1	0.40	<10	0.84	1506	<2	0.01	2	1393	54	3.07	5	2	88	<5	0.01	<10	<10	29	<10	221	3
84334	1.5	1.42	214	127	<0.5	<5	6.11	5	17	28	44	4.49	<1	0.38	<10	0.69	2182	<2	0.01	2	1438	91	3.46	6	2	175	<5	0.01	<10	<10	33	<10	316	3
84335	2.3	0.93	205	101	<0.5	<5	4.30	2	16	23	19	4.72	<1	0.40	<10	0.36	1479	<2	0.01	2	1299	35	4.17	<5	2	137	5	0.03	<10	<10	18	<10	47	3
84336	0.4	1.51	82	132	<0.5	<5	6.55	2	15	16	21	4.34	<1	0.33	<10	0.79	2428	<2	0.02	2	1245	38	2.29	<5	3	190	<5	0.03	<10	<10	36	<10	39	3
84337	0.8	1.78	154	120	<0.5	<5	5.27	2	19	17	51	5.62	<1	0.33	<10	1.00	1996	<2	0.01	3	1182	21	3.25	5	3	138	<5	0.03	<10	13	42	<10	44	3
84338	0.6	1.92	71	139	<0.5	<5	4.66	2	16	15	33	4.49	<1	0.35	<10	1.02	1833	<2	0.02	2	1205	13	1.57	<5	3	132	6	0.03	<10	<10	43	<10	54	3
84339	0.8	1.80	111	119	<0.5	<5	4.45	2	18	19	34	4.57	<1	0.32	<10	0.99	1927	<2	0.02	3	1099	21	1.81	<5	3	118	5	0.03	<10	<10	49	<10	60	3
84340	1.3	1.17	294	126	<0.5	<5	5.19	2	18	32	16	4.57	<1	0.33	<10	0.52	1946	3	0.01	2	1134	33	3.66	<5	2	145	<5	0.05	<10	10	25	<10	33	3
84341	10.2	1.37	404	137	<0.5	<5	3.61	14	13	48	348	4.74	<1	0.28	<10	0.65	1978	<2	0.01	2	919	1000	2.97	11	1	129	<5	0.02	<10	12	26	<10	1318	3
84342	3.7	0.87	784	103	<0.5	<5	3.47	5	8	83	48	3.33	<1	0.23	<10	0.42	1641	2	0.01	2	606	345	1.83	11	1	162	<5	0.03	<10	<10	21	<10	503	2
84343	9.3	0.85	297	96	<0.5	<5	1.52	21	11	77	467	4.66	<1	0.22	<10	0.48	990	4	0.01	2	619	342	3.73	7	1	30	<5	0.05	<10	<10	27	<10	2367	3
84344	4.2	1.52	128	115	<0.5	<5	5.56	5	13	56	66	4.01	<1	0.28	<10	0.78	2871	3	0.01	1	812	58	1.21	5	2	427	<5	0.06	<10	11	38	<10	509	2
84345	1.1	2.45	41	120	<0.5	<5	4.63	3	18	12	45	5.37	<1	0.35	<10	1.32	2584	<2	0.02	2	1193	37	0.83	<5	4	147	<5	0.11	<10	11	72	<10	189	4
84346	2.0	2.28	149	115	<0.5	<5	4.82	9	18	13	49	5.38	<1	0.32	<10	1.20	2528	<2	0.02	1	1180	261	1.26	<5	3	153	<5	0.07	<10	12	69	<10	738	3
84347	2.0	2.31	36	145	<0.5	<5	0.67	3	20	14	35	5.76	<1	0.18	<10	1.62	2549	<2	0.02	3	1160	23	1.06	<5	6	21	5	0.01	<10	10	191	<10	155	3
84348	2.5	1.72	74	130	<0.5	<5	7.30	3	17	15	56	5.18	<1	0.26	<10	0.95	3309	<2	0.01	2	907	342	1.94	<5	4	291	<5	0.01	<10	18	83	<10	170	3
84349	2.0	2.50	34	119	<0.5	<5	3.78	2	25	6	82	6.13	<1	0.35	<10	1.40	3552	<2	0.02	3	1237	38	1.42	<5	6	199	5	0.01	<10	17	114	<10	96	4
84350	<0.2	1.07	<5	243	<0.5	<5	0.56	<1	7	114	<1	2.18	<1	0.54	<10	0.62	606	<2	0.08	5	652	4	<0.01	<5	3	47	8	0.14	19	<10	41	<10	50	2
84351	1.8	2.86	15	117	<0.5	<5	3.08	3	28	<1	109	6.43	<1	0.33	<10	1.64	2902	<2	0.02	3	1261	66	0.76	<5	7	154	<5	0.02	<10	16	151	<10	113	4
84352	3.2	3.63	63	300	<0.5	<5	6.22	4	35	11	96	8.77	<1	0.49	13	2.07	4370	4	0.03	4	1906	70	1.75	5	9	300	<5	0.01	<10	31	145	<10	168	5
84353	55.1	2.09	155	113	<0.5	<5	3.24	4	23	5	68	5.41	<1	0.29	<10	1.19	2485	<2	0.02	3	1155	131	1.56	5	5	156	5	0.01	<10	11	96	<10	365	3
84354	1.5	1.37	19	109	<0.5	<5	4.26	3	19	5	56	5.81	<1	0.40	<10	1.10	2265	3	0.02	2	905	51	0.78	<5	5	231	<5	<0.01	<10	15	43	<10	100	3
84355	3.8	1.62	60	169	<0.5	<5	1.84	27	18	6	117	5.94	<1	0.38	<10	0.65	1727	46	0.02	3	1078	110	0.74	<5	5	57	<5	<0.01	<10	13	52	<10	846	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2558RJ

Date : Aug-01-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment1-12bags

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84356	10.4	1.08	192	104	<0.5	<5	3.73	7	15	21	331	5.35	<1	0.30	<10	0.99	2124	46	0.01	3	1112	70	1.43	6	4	205	<5	<0.01	<10	16	34	<10	508	3
84357	100.2	0.54	279	112	<0.5	<5	4.25	21	13	75	322	5.06	<1	0.31	<10	0.63	1763	61	0.01	4	790	750	2.66	24	2	274	<5	<0.01	<10	20	16	<10	2277	3
84358	5.7	0.53	68	160	<0.5	<5	5.17	3	14	20	94	4.33	<1	0.36	<10	0.99	2307	10	0.02	1	1326	30	0.95	<5	3	281	<5	<0.01	<10	18	14	<10	114	2
84359	5.6	0.51	73	96	<0.5	<5	5.59	3	14	22	119	4.54	<1	0.33	<10	1.10	2606	15	0.02	2	1111	34	0.92	5	3	312	<5	<0.01	<10	16	16	<10	122	2
84360	2.6	0.79	59	113	<0.5	<5	3.93	2	15	15	81	4.32	<1	0.36	<10	0.92	1978	17	0.02	2	1361	15	0.92	<5	4	211	<5	<0.01	<10	10	18	<10	91	2
84361	0.6	1.00	54	207	<0.5	<5	3.88	1	18	20	62	4.27	<1	0.36	<10	0.93	2021	33	0.02	2	1361	11	0.85	<5	3	200	<5	<0.01	<10	<10	27	<10	81	3
84362	1.2	1.32	97	122	<0.5	<5	2.27	1	19	30	43	4.10	<1	0.30	<10	0.76	1520	11	0.01	2	1096	47	1.27	<5	2	76	<5	<0.01	<10	<10	33	<10	111	2
84363	3.2	1.55	263	132	<0.5	<5	3.20	4	19	16	96	4.55	<1	0.34	<10	0.83	1728	9	0.01	3	1223	88	1.10	7	2	100	<5	<0.01	<10	13	36	<10	389	2
84364	6.6	1.65	152	137	<0.5	<5	3.94	5	15	17	187	4.95	<1	0.36	<10	0.85	1961	16	0.01	1	1304	185	1.69	<5	3	127	<5	<0.01	<10	17	49	<10	435	3
84365	4.4	1.88	31	168	<0.5	<5	4.23	3	18	14	225	5.10	<1	0.36	<10	0.83	2011	33	0.01	1	1208	92	0.81	<5	3	122	<5	0.01	<10	18	55	<10	293	3
84366	2.3	2.01	38	174	<0.5	<5	5.51	3	19	5	297	5.37	<1	0.38	<10	1.01	2332	27	0.01	2	1491	27	0.88	<5	4	217	<5	0.01	<10	22	65	<10	208	3
84367	2.1	2.15	30	180	<0.5	<5	5.74	4	16	1	298	5.82	<1	0.38	<10	1.09	2408	34	0.02	1	1489	19	0.92	<5	4	251	<5	0.01	<10	20	69	<10	248	3
84368	2.4	1.35	220	186	<0.5	<5	6.53	4	19	6	179	4.24	<1	0.35	<10	0.80	2650	23	0.01	2	1340	51	1.48	<5	3	261	<5	0.01	<10	18	39	<10	212	3
84369	2.4	1.78	61	135	<0.5	<5	4.74	4	17	7	196	5.17	<1	0.38	<10	0.91	2344	43	0.01	1	1291	51	1.36	<5	3	138	<5	<0.01	<10	19	58	<10	276	3
84370	2.3	1.88	30	133	<0.5	<5	6.05	3	18	6	198	5.33	<1	0.35	<10	0.96	2394	34	0.02	2	1234	14	1.02	<5	4	327	<5	<0.01	<10	23	56	<10	184	3
84371	32.8	1.04	128	103	<0.5	<5	4.19	13	16	21	184	5.44	<1	0.31	<10	0.78	1993	35	0.01	2	1211	388	3.34	<5	3	294	<5	<0.01	<10	21	32	<10	1560	3
84372	22.1	1.40	46	213	0.5	<5	4.68	16	19	6	361	5.23	<1	0.44	<10	0.47	2052	26	0.01	1	1447	1185	0.84	<5	3	96	<5	<0.01	<10	16	30	<10	1879	3
139036	10.3	0.49	283	218	<0.5	<5	0.09	8	4	90	81	6.18	<1	0.18	<10	0.22	426	6	0.01	2	577	1410	1.23	11	1	10	<5	0.01	<10	16	27	<10	1219	3
139037	12.3	0.70	232	212	<0.5	<5	0.10	7	5	72	86	6.09	<1	0.17	<10	0.40	554	20	0.01	1	661	1553	1.40	8	1	9	<5	0.01	<10	18	39	<10	868	3
139038	5.2	1.17	254	129	<0.5	<5	0.10	16	7	80	116	5.69	<1	0.13	<10	0.73	1234	20	0.01	2	697	601	1.59	5	2	9	<5	0.02	<10	19	57	<10	2370	3
139039	6.5	1.75	228	127	<0.5	<5	0.20	5	11	50	85	6.36	<1	0.15	<10	1.15	1649	13	0.01	1	943	312	1.51	<5	3	11	<5	0.02	<10	20	72	<10	516	4
139040	14.2	0.71	336	127	<0.5	<5	1.64	12	8	83	87	5.82	<1	0.14	<10	0.37	1505	17	0.01	2	524	1737	2.22	7	2	77	<5	0.01	<10	19	30	<10	1715	3
139041	14.6	0.74	404	171	<0.5	<5	0.11	3	9	70	33	5.74	<1	0.20	<10	0.40	873	29	0.01	1	668	506	1.53	6	1	11	<5	0.01	<10	17	34	<10	232	3
139042	15.8	0.48	348	79	<0.5	<5	0.73	6	14	78	62	6.35	<1	0.12	<10	0.26	1116	14	0.01	2	422	599	3.46	8	1	15	<5	<0.01	<10	21	19	<10	662	3
139043	6.4	0.72	313	110	<0.5	<5	2.50	10	9	87	92	4.59	<1	0.13	<10	0.40	1913	8	0.01	2	502	1122	2.34	8	2	55	<5	0.01	<10	16	33	<10	1308	3
139044	40.9	0.29	653	114	<0.5	6	0.07	4	7	125	60	7.48	<1	0.20	<10	0.10	302	23	0.01	2	429	1789	2.37	14	1	10	<5	<0.01	<10	24	21	<10	522	4
139045	5.5	0.75	524	168	<0.5	<5	0.15	3	4	93	62	4.64	<1	0.15	<10	0.43	958	22	0.01	2	508	454	1.19	7	1	8	<5	<0.01	<10	15	37	<10	414	3
139046	3.1	0.84	295	168	<0.5	<5	0.09	2	4	154	23	3.54	<1	0.13	<10	0.56	982	13	0.01	4	545	196	0.33	7	2	5	<5	<0.01	<10	10	38	<10	177	2
139047	1.2	2.45	86	152	<0.5	<5	0.70	4	15	28	32	6.32	<1	0.27	<10	1.67	2610	7	0.01	2	1286	84	1.48	<5	4	12	<5	0.07	<10	18	86	<10	332	4
139048	22.8	1.63	324	57	<0.5	<5	1.29	51	18	76	651	9.41	<1	0.23	<10	1.00	1979	8	0.01	2	1026	2950	>5.00	17	3	26	<5	0.02	<10	32	80	<10	5530	6

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2558RJ**

Date : Aug-01-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment1-12bags

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139049	12.9	1.91	693	40	<0.5	8	0.16	22	6	52	94	11.04	<1	0.11	<10	1.60	2069	8	0.01	2	892	2058	>5.00	14	3	6	<5	0.01	<10	42	100	<10	2538	7
139050	1.3	2.26	61	171	<0.5	<5	0.38	4	14	44	60	5.91	<1	0.22	<10	1.36	2485	14	0.01	3	1250	158	0.46	5	6	5	<5	0.02	<10	16	143	<10	511	4
139051	12.7	0.43	164	124	<0.5	<5	0.08	2	5	189	237	3.96	<1	0.22	<10	0.13	707	8	0.01	5	692	1477	1.06	13	1	<1	<5	0.01	<10	10	17	<10	217	2
139052	60.6	0.27	176	111	<0.5	<5	0.04	13	5	137	791	5.25	<1	0.21	<10	0.06	293	9	0.01	3	638	9192	2.35	30	1	<1	<5	<0.01	<10	14	17	<10	2600	3
139053	20.3	0.20	127	48	<0.5	<5	0.18	15	4	250	319	3.09	<1	0.11	<10	0.07	624	7	0.01	7	196	3944	1.85	18	<1	2	<5	<0.01	<10	10	5	<10	3163	2
139054	11.1	0.56	87	41	<0.5	<5	0.14	2	3	167	49	3.15	<1	0.11	<10	0.31	1944	7	<0.01	5	192	1338	1.06	11	<1	3	<5	<0.01	<10	16	12	<10	381	2
139055	9.5	0.69	193	112	<0.5	<5	0.17	4	8	226	62	5.16	<1	0.21	<10	0.36	2247	19	0.01	7	660	912	2.57	10	2	7	<5	0.02	<10	18	33	<10	401	3
139056	8.1	0.78	154	140	<0.5	<5	0.12	3	7	128	50	4.23	<1	0.20	<10	0.39	3726	8	0.01	4	607	633	1.44	7	1	4	<5	0.01	<10	22	27	<10	273	3
139057	8.9	0.82	131	159	<0.5	<5	0.21	3	8	191	78	4.29	<1	0.22	<10	0.39	3262	10	0.01	6	739	500	1.53	8	2	5	<5	0.03	<10	19	32	<10	313	3
139058	6.4	0.95	236	153	<0.5	<5	0.26	2	8	113	67	3.91	<1	0.20	<10	0.53	2898	7	0.01	4	736	247	1.09	6	2	6	<5	0.04	<10	15	36	<10	164	3
139059	1.5	1.87	157	179	<0.5	<5	1.67	5	22	75	86	4.63	<1	0.26	<10	1.37	4057	19	0.01	10	1163	103	1.26	5	4	48	<5	0.05	<10	20	81	<10	375	3
139060	56.5	0.37	1132	31	<0.5	14	0.96	90	10	129	929	12.59	<1	0.09	<10	0.26	1591	6	0.01	4	273	>10000	>5.00	35	<1	23	<5	0.01	<10	52	21	<10	>10000	8
139061	25.9	0.64	641	40	<0.5	9	1.46	141	11	139	516	10.80	<1	0.13	<10	0.46	2050	8	0.01	3	485	>10000	>5.00	20	1	33	<5	0.02	<10	46	38	<10	>10000	7
139062	18.7	0.73	491	38	<0.5	8	1.19	81	8	122	360	9.98	<1	0.14	<10	0.49	2006	<2	0.01	4	435	>10000	>5.00	16	1	23	<5	0.02	<10	39	38	<10	>10000	6
139063	9.2	1.07	381	53	<0.5	5	1.71	34	12	126	169	7.52	<1	0.22	<10	0.63	3259	3	0.01	7	426	3988	>5.00	12	2	35	<5	0.03	<10	34	39	<10	3917	5
SD0805	21.4	0.12	113	103	<0.5	<5	0.05	22	5	187	256	2.82	<1	0.13	<10	0.02	148	3	0.01	6	396	7794	1.96	16	<1	<1	<5	0.01	<10	<10	5	<10	4640	2
SD0806	11.6	1.80	130	70	<0.5	<5	2.20	42	15	165	84	6.08	<1	0.21	<10	1.24	5448	<2	0.01	13	891	7691	4.25	12	4	50	<5	0.01	<10	34	58	<10	8842	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2596-RA1

Company: **Ascot Resources Ltd**
 Project: **Dilworth/Shipment 11**
 Attn: **Sue Deane**

Aug-06-08

We hereby certify the following assay of 24 core samples submitted Jul-21-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
84373	0.10	0.10	6.0	
84374	0.35		2.4	
84375	0.10		>200	744.1
84376	0.41		1.4	
84377	0.46		3.2	
84378	0.54		2.0	
84379	0.33		2.5	
84380	0.48		1.3	
84381	0.19		2.3	
84382	0.02	0.02	0.7	
84383	0.01		0.6	
84384	0.01		0.5	
84385	0.01		0.2	
84386	0.02		0.6	
84387	0.15		51.0	
84388	0.26		2.3	
84389	0.08		1.7	
84390	0.01		0.3	
84391	0.02		0.7	
84392	0.03	0.02	0.7	
84393	0.04		4.4	
84394	0.03		0.4	
84395	0.01		0.7	
84396	0.03		0.5	
*0218	0.88			
*CCu-1c				128.4
*BLANK	<0.01			<0.1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2596-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 11**
Attn: **Sue Deane**

Aug-06-08

We hereby certify the following assay of 24 core samples submitted Jul-21-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84397	0.02	0.02	0.4
84398	0.03		1.0
84399	0.01		0.4
84400	<0.01		<0.1
84401	0.02		0.9
84402	0.02		0.6
84403	0.01		0.7
84404	0.02		0.8
84405	<0.01		0.4
84406	<0.01	0.01	0.3
84407	<0.01		0.3
84408	0.01		0.2
84409	<0.01		0.3
84410	<0.01		0.2
84411	0.01		0.2
84412	<0.01		0.6
84413	0.01		0.9
84414	0.02		1.1
84415	0.03		0.8
84416	0.02	0.02	1.0
84417	0.11		1.1
84418	0.05		0.9
84419	0.02		0.7
*0218	0.88		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2596-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 11**
Attn: **Sue Deane**

Aug-06-08

We hereby certify the following assay of 24 core samples submitted Jul-21-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84420	0.02	0.03	3.3
84421	0.01		1.3
84494	0.01		0.5
84495	0.03		1.1
84496	<0.01		0.9
84497	<0.01		0.5
84498	0.06		21.3
84499	0.01		1.1
84500	<0.01		<0.1
84501	0.01	0.01	0.2
84502	0.02		0.9
84503	0.03		1.0
84504	0.02		1.0
84505	0.05		1.4
84506	0.05		3.3
84507	0.05		1.1
84508	0.05		0.6
84509	0.05		0.3
84510	0.03		0.6
84511	0.05	0.04	1.2
84512	0.02		1.0
84513	0.01		<0.1
84514	0.01		0.1
84515	0.02		0.2
*0218	0.90		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2596-RA4

Company: **Ascot Resources Ltd**
 Project: **Dilworth/Shipment 11**
 Attn: **Sue Deane**

Aug-06-08

We hereby certify the following assay of 24 core samples submitted Jul-21-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne	Pb %
84516	0.02	0.01	<0.1		
84517	<0.01		0.4		
84518	0.01		<0.1		
84519	0.02		1.7		
84520	0.01		<0.1		
84521	0.01		<0.1		
84522	0.01		<0.1		
84523	0.01		<0.1		
84524	<0.01		<0.1		
84525	1.32	1.27	>200	230.3	
84526	<0.01		<0.1		
84527	0.02		<0.1		
84528	0.01		0.2		
84529	0.01		0.5		
84530	0.02		<0.1		
84531	0.10		1.4		
84532	0.05		0.6		
84533	0.22		1.5		
139064	0.49		18.8		
139065	0.41	0.41	23.7		0.99
139066	0.36		12.8		
139067	0.28		5.8		
139068	0.11		2.8		
139069	0.09		3.4		
*0218	0.87				
*CCu-1c				130.2	0.34
*BLANK	<0.01			<0.1	<0.01

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2596-RA5

Company: **Ascot Resources Ltd**
 Project: **Dilworth/Shipment 11**
 Attn: **Sue Deane**

Aug-06-08

We hereby certify the following assay of 24 core samples submitted Jul-21-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
139070	0.20	0.19	16.5	
139071	0.15		16.5	
139072	0.67		36.5	1.22
139073	0.05		0.6	
139074	0.05		0.6	
139075	0.03		0.5	
139076	0.08		2.3	
139077	0.20		5.2	
139078	0.04		1.5	
139079	0.05	0.03	0.6	
139080	0.06		0.6	
139081	0.06		0.7	
139082	0.07		0.8	
139083	0.02		<0.1	
139084	0.01		0.2	
139085	<0.01		0.3	
139086	0.02		0.7	
139087	0.02		0.2	
139088	0.03		0.5	
139089	0.02	0.01	0.2	
139090	0.03		0.5	
139091	0.03		1.5	
139092	0.03		7.4	
139093	0.04		7.9	
*0218	0.93			
*CCu-1c				3.96
*BLANK	<0.01			<0.01

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2596-RA6

Company: **Ascot Resources Ltd**
 Project: **Dilworth/Shipment 11**
 Attn: **Sue Deane**

Aug-06-08

We hereby certify the following assay of 24 core samples submitted Jul-21-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne	Pb %	Zn %
139094	0.08	0.09	9.6			
139095	1.36		>200	1736		1.03
139096	0.17		86.7			
139097	0.06		5.8			
139098	0.01		4.9			
139099	0.03		9.6			
139100	0.02		0.5			
139101	2.23		26.8			10.1
139102	0.02		0.5			
139103	1.10	1.09	12.2			8.10
139104	0.58		58.7		2.64	
139105	0.42		3.4			
139106	0.03		0.8			
SD0807	0.69		35.2			
SD0808	6.17		103		1.15	
SD0809	0.17		8.9			2.99
*0218	0.92					
*CCu-1c				129.7	0.34	3.96
*BLANK	<0.01			<0.1	<0.01	<0.01

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2596-RA7

Company: **Ascot Resources Ltd**
Project: Dilworth/Shipment 11
Attn: Sue Deane

Aug-06-08

We *hereby certify* the following assay of 24 core samples
submitted Jul-21-08

Sample Name	Au g/tonne	ICP %
------------------------	-----------------------	------------------

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2596-RA8

Company: **Ascot Resources Ltd**
Project: Dilworth/Shipment 11
Attn: Sue Deane

Aug-06-08

We hereby certify the following assay of 24 core samples
submitted Jul-21-08

Sample Name	Au g/tonne	ICP %
------------------------	-----------------------	------------------

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2596-RA9

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 11**
Attn: **Sue Deane**

Aug-06-08

We *hereby certify* the following assay of 16 core samples
submitted Jul-21-08

Sample Name	Au g/tonne	ICP %
------------------------	-----------------------	------------------

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2596RJ

Date : Aug-06-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 11

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84373	6.0	1.48	36	138	<0.5	<5	5.75	1	19	16	538	4.82	<1	0.37	<10	1.04	2394	86	0.01	1	1551	21	0.72	<5	4	260	<5	<0.01	<10	<10	34	<10	213	2
84374	2.4	0.92	38	114	<0.5	<5	3.87	1	15	16	194	3.99	<1	0.32	<10	0.83	1820	19	0.01	1	1671	26	0.62	<5	3	207	<5	<0.01	<10	<10	19	<10	211	2
84375	>200.0	0.80	586	200	<0.5	114	0.61	17	8	175	6993	2.40	6	0.26	<10	0.57	337	578	0.06	6	628	937	1.29	1461	2	83	<5	0.06	<10	<10	29	<10	1004	3
84376	1.4	1.21	11	112	<0.5	<5	3.68	<1	13	19	79	3.94	<1	0.29	10	0.94	1613	15	0.02	1	1599	13	0.19	<5	3	183	<5	<0.01	<10	<10	34	<10	209	2
84377	3.2	1.01	43	116	<0.5	<5	4.42	1	13	19	107	4.04	<1	0.32	<10	1.00	1865	22	0.02	1	1599	15	0.33	<5	3	291	<5	<0.01	<10	<10	24	<10	214	2
84378	2.0	1.37	20	72	<0.5	<5	4.76	<1	12	36	244	3.83	<1	0.21	10	0.80	1739	18	0.02	1	1569	15	0.26	<5	3	267	<5	<0.01	<10	<10	45	<10	206	2
84379	2.5	1.01	109	130	<0.5	<5	3.43	2	14	23	170	4.43	<1	0.28	<10	0.59	1931	20	0.01	1	1654	16	0.66	<5	3	78	<5	<0.01	<10	<10	25	<10	216	2
84380	1.3	1.67	27	90	0.5	<5	3.31	1	14	17	149	4.23	<1	0.28	10	0.97	1631	14	0.02	<1	1681	64	0.50	<5	3	107	<5	0.01	<10	<10	48	<10	330	2
84381	2.3	1.59	26	64	<0.5	<5	3.23	<1	13	12	271	4.24	<1	0.24	<10	0.92	1684	20	0.02	<1	1726	14	0.57	<5	3	83	<5	0.03	<10	<10	50	<10	219	2
84382	0.7	2.71	469	51	0.5	<5	7.55	6	31	49	108	6.30	1	0.09	<10	2.72	2847	<2	0.01	14	1895	48	1.97	<5	18	183	<5	0.06	<10	<10	242	<10	108	3
84383	0.6	2.15	557	57	0.6	<5	9.42	8	30	41	72	5.39	<1	0.10	<10	2.01	2599	<2	0.01	12	1686	30	1.68	<5	18	215	<5	0.07	<10	<10	211	<10	88	4
84384	0.5	2.34	325	54	<0.5	<5	7.28	5	30	45	104	6.34	<1	0.11	<10	2.25	2444	<2	0.01	13	1891	46	2.09	<5	17	193	<5	0.04	<10	<10	229	<10	156	3
84385	0.2	2.94	83	48	0.6	<5	6.72	3	28	42	92	6.46	<1	0.08	<10	2.82	2462	<2	0.01	12	1891	155	1.78	<5	18	138	<5	0.10	<10	<10	251	<10	328	4
84386	0.6	2.62	107	51	0.5	<5	6.27	4	29	40	100	6.19	1	0.09	<10	2.56	2319	<2	0.01	13	1833	194	2.13	<5	16	137	<5	0.08	<10	<10	223	<10	370	3
84387	51.0	1.05	3572	59	<0.5	<5	>15.00	127	14	21	1910	5.25	<1	0.13	<10	1.46	4347	<2	0.01	8	1139	6859	2.29	188	12	1017	<5	<0.01	<10	<10	68	88	6825	2
84388	2.3	2.62	2802	53	<0.5	<5	8.98	51	24	42	84	5.70	<1	0.08	<10	2.39	3345	<2	0.01	12	1591	459	0.75	14	17	195	<5	0.02	<10	<10	219	11	718	3
84389	1.7	2.60	847	61	0.7	<5	7.99	16	30	40	104	5.78	<1	0.11	<10	2.51	2515	<2	0.01	13	1851	396	1.79	<5	16	178	<5	0.12	<10	<10	231	<10	452	3
84390	0.3	2.30	136	55	0.6	<5	8.39	2	26	39	70	5.31	<1	0.09	<10	2.19	2397	<2	0.01	12	1600	87	1.56	<5	15	158	<5	0.11	<10	<10	204	<10	158	3
84391	0.7	2.54	205	55	0.7	<5	10.28	5	25	37	74	5.10	<1	0.16	<10	2.20	2775	<2	0.01	12	1634	104	0.80	<5	14	194	<5	0.11	<10	<10	179	<10	287	3
84392	0.7	2.68	99	48	0.6	<5	7.83	5	28	35	92	5.28	<1	0.17	<10	2.45	2523	<2	0.01	12	1763	28	0.88	<5	11	152	<5	0.10	<10	<10	172	<10	513	3
84393	4.4	2.80	151	39	0.7	<5	8.70	32	31	40	415	5.92	<1	0.13	<10	2.55	2686	2	0.01	12	1609	576	1.57	<5	12	148	<5	0.11	<10	<10	180	38	2880	3
84394	0.4	2.48	57	43	0.8	<5	8.92	1	25	37	67	5.17	<1	0.15	<10	2.19	2405	<2	0.01	11	1659	27	0.77	<5	14	162	<5	0.12	<10	<10	185	<10	122	3
84395	0.7	2.57	69	46	0.7	<5	7.96	3	28	34	100	5.50	<1	0.15	<10	2.17	2174	<2	0.01	11	1648	54	0.92	<5	12	143	<5	0.12	<10	<10	173	<10	311	3
84396	0.5	2.52	94	48	0.8	<5	7.77	2	31	32	84	5.63	<1	0.16	<10	2.10	2225	<2	0.01	13	1920	38	1.31	<5	12	140	<5	0.14	<10	<10	183	<10	192	4
84397	0.4	2.35	70	70	0.9	<5	10.27	1	26	48	53	5.15	<1	0.20	<10	1.74	2301	<2	0.01	10	1598	36	0.90	<5	11	201	<5	0.14	<10	<10	142	<10	131	4
84398	1.0	2.69	119	221	1.0	<5	7.10	4	29	41	89	5.50	<1	0.27	<10	2.01	2446	<2	0.01	11	1766	369	0.78	<5	11	119	<5	0.15	<10	<10	162	<10	379	3
84399	0.4	2.73	124	60	1.0	<5	8.62	2	27	50	70	5.61	<1	0.15	<10	2.51	2427	<2	0.01	12	1664	65	0.99	<5	16	154	<5	0.15	<10	<10	214	<10	191	5
84400	<0.2	1.10	<5	366	1.0	<5	0.69	<1	9	158	2	2.33	<1	0.51	10	0.64	653	<2	0.08	7	893	29	0.01	<5	3	61	<5	0.17	<10	<10	44	<10	62	3
84401	0.9	2.27	1413	262	0.7	<5	11.28	22	25	45	84	5.33	<1	0.07	<10	1.98	3077	<2	0.01	12	1554	134	1.31	9	16	167	<5	0.11	<10	<10	213	<10	248	4
84402	0.6	1.98	2038	66	0.9	<5	9.12	30	30	44	100	5.79	<1	0.08	<10	1.69	2684	<2	0.01	13	1680	46	2.39	21	18	148	<5	0.14	<10	<10	233	<10	82	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2596RJ

Date : Aug-06-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 11

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84403	0.7	2.22	192	85	1.0	<5	8.40	2	29	61	105	6.24	<1	0.10	<10	1.95	2676	<2	0.01	14	1734	43	2.66	<5	17	117	<5	0.16	<10	<10	230	<10	90	5
84404	0.8	1.53	93	46	0.7	<5	>15.00	2	18	32	36	3.99	<1	0.12	<10	0.99	3243	<2	0.01	9	1160	72	0.80	<5	10	235	<5	0.08	<10	<10	114	<10	118	4
84405	0.4	1.88	98	85	1.1	<5	9.03	2	31	40	87	5.43	<1	0.09	<10	1.40	2627	<2	0.02	14	1945	45	1.92	<5	19	151	<5	0.17	<10	<10	240	<10	199	8
84406	0.3	2.30	77	70	0.9	<5	9.20	1	26	44	75	5.49	1	0.06	<10	1.96	2443	<2	0.01	12	1660	25	1.13	<5	17	143	<5	0.14	<10	<10	232	<10	157	5
84407	0.3	2.42	113	50	1.0	<5	9.10	2	30	44	81	5.92	<1	0.05	<10	2.02	2642	<2	0.02	13	1761	32	1.29	<5	20	153	<5	0.17	<10	<10	257	<10	148	5
84408	0.2	2.31	85	65	0.9	<5	6.97	1	31	55	96	5.89	<1	0.05	<10	2.14	2213	<2	0.02	14	1861	60	1.90	<5	21	122	<5	0.16	<10	<10	285	<10	144	6
84409	0.3	2.38	66	57	0.9	<5	6.64	2	31	58	105	5.63	<1	0.06	<10	2.25	2250	<2	0.02	13	1800	126	1.47	<5	22	142	<5	0.16	<10	<10	271	<10	231	6
84410	0.2	2.62	94	53	1.0	<5	9.10	1	29	42	77	5.96	<1	0.08	<10	2.26	2681	<2	0.02	13	1797	26	1.01	<5	21	165	<5	0.16	<10	<10	255	<10	157	5
84411	0.2	2.63	85	56	1.0	<5	6.17	2	29	45	90	5.95	<1	0.06	<10	2.34	2515	<2	0.02	13	1834	56	1.13	<5	22	130	<5	0.16	<10	<10	267	<10	262	5
84412	0.6	2.27	81	71	0.7	<5	7.48	3	28	34	76	5.05	<1	0.21	<10	1.71	2488	<2	0.01	12	1777	135	0.85	<5	12	150	<5	0.12	<10	<10	166	<10	377	3
84413	0.9	2.27	104	75	<0.5	<5	9.49	2	23	37	73	5.10	<1	0.25	<10	1.63	2859	<2	0.01	11	1480	86	0.77	<5	10	171	<5	0.03	<10	<10	138	<10	224	3
84414	1.1	1.20	298	166	<0.5	<5	13.37	9	21	19	59	4.55	<1	0.25	<10	1.49	3246	<2	0.01	10	1433	200	0.85	<5	10	260	<5	<0.01	<10	<10	88	<10	546	2
84415	0.8	2.63	154	77	0.5	<5	9.19	2	28	36	80	5.79	<1	0.19	<10	2.26	3121	<2	0.01	12	1679	36	1.55	<5	12	175	<5	0.06	<10	<10	168	<10	125	3
84416	1.0	2.75	173	72	0.5	<5	9.59	6	24	33	86	5.85	<1	0.20	<10	2.45	3362	<2	0.01	11	1591	36	1.34	<5	12	190	<5	0.05	<10	<10	163	<10	425	3
84417	1.1	1.95	228	89	0.8	<5	8.07	14	28	32	52	5.91	<1	0.25	<10	1.56	3333	<2	0.01	13	1755	24	3.59	<5	9	154	<5	0.11	<10	<10	128	20	1457	4
84418	0.9	2.29	329	71	0.6	<5	4.40	6	31	34	78	6.93	<1	0.28	<10	2.06	2930	<2	0.01	15	1917	33	4.48	<5	8	87	<5	0.09	<10	<10	138	<10	260	4
84419	0.7	2.76	176	74	0.8	<5	7.85	9	30	35	102	6.10	<1	0.18	<10	2.38	3412	<2	0.01	13	1714	14	1.64	<5	12	184	<5	0.13	<10	<10	181	11	740	4
84420	3.3	2.99	149	282	<0.5	<5	7.20	12	25	37	130	6.52	1	0.16	<10	2.24	3342	<2	0.01	10	1518	967	1.80	<5	11	175	<5	0.08	<10	<10	170	15	989	4
84421	1.3	3.03	101	396	0.7	<5	5.79	4	30	42	101	6.06	<1	0.24	<10	2.56	2703	<2	0.01	14	1799	98	1.36	<5	11	142	<5	0.10	<10	<10	184	<10	336	4
84494	0.5	2.62	432	233	0.6	<5	7.01	7	29	47	80	5.60	1	0.18	<10	2.37	2538	<2	0.01	12	1815	49	1.48	<5	17	168	<5	0.08	<10	<10	221	<10	142	5
84495	1.1	2.38	410	180	0.5	<5	9.09	6	28	42	93	5.64	1	0.17	<10	2.09	2642	<2	0.01	13	1787	66	1.91	<5	16	215	<5	0.06	<10	<10	215	<10	139	5
84496	0.9	2.51	134	271	0.5	<5	9.32	2	30	41	98	5.96	<1	0.11	<10	2.58	2925	<2	0.02	13	1772	51	1.56	<5	21	308	<5	0.06	<10	<10	218	<10	125	5
84497	0.5	3.13	53	103	0.7	<5	7.14	<1	32	51	95	6.47	<1	0.11	<10	3.03	2751	<2	0.02	14	1868	34	1.89	<5	23	178	<5	0.10	<10	<10	263	<10	80	6
84498	21.3	2.14	2784	58	<0.5	<5	>15.00	120	14	25	679	5.13	<1	0.11	<10	1.66	4223	<2	0.01	5	846	8088	1.78	46	9	1144	<5	<0.01	<10	<10	91	87	6270	3
84499	1.1	2.93	921	87	0.6	<5	8.14	17	25	46	85	5.72	<1	0.08	<10	2.75	3198	<2	0.01	12	1646	294	1.13	8	19	252	<5	0.08	<10	<10	249	<10	357	4
84500	<0.2	1.08	7	396	0.9	<5	0.76	<1	9	152	6	2.30	<1	0.51	<10	0.71	699	2	0.08	7	871	63	0.05	<5	3	53	<5	0.15	<10	<10	49	<10	113	2
84501	0.2	2.72	90	62	0.7	<5	9.58	2	31	47	114	5.97	1	0.05	<10	2.41	2693	<2	0.02	13	1773	92	1.53	<5	20	277	<5	0.11	<10	<10	278	<10	137	5
84502	0.9	2.65	321	66	0.7	<5	8.82	5	28	53	97	5.50	1	0.11	<10	2.59	2669	<2	0.01	13	1816	79	1.72	5	16	222	<5	0.11	<10	<10	227	<10	143	5
84503	1.0	2.57	345	52	0.6	<5	10.93	8	28	35	88	5.19	<1	0.13	<10	2.31	3058	<2	0.01	11	1577	121	1.22	<5	13	228	<5	0.09	<10	<10	181	<10	392	4
84504	1.0	2.74	176	65	0.8	<5	9.60	4	28	42	81	5.56	<1	0.21	<10	2.23	2929	<2	0.01	13	1767	80	1.03	<5	13	206	<5	0.11	<10	<10	183	<10	212	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2596RJ**

Date : Aug-06-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 11

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84505	1.4	2.68	104	57	0.6	<5	8.73	15	29	40	193	5.40	<1	0.20	<10	2.13	2917	<2	0.01	12	1717	108	0.81	<5	11	165	<5	0.09	<10	<10	167	19	1260	3
84506	3.3	2.73	162	61	0.5	<5	6.90	24	24	39	139	5.96	<1	0.20	<10	2.04	2794	<2	0.01	11	1561	1167	1.59	<5	11	126	<5	0.08	<10	<10	165	28	2059	4
84507	1.1	2.92	147	59	0.6	<5	6.28	6	31	44	104	6.52	<1	0.24	<10	2.36	2513	<2	0.01	14	1798	70	2.20	<5	11	113	<5	0.08	<10	<10	174	<10	547	4
84508	0.6	2.82	367	46	0.6	<5	10.84	6	23	39	71	5.59	<1	0.17	<10	2.40	2697	<2	0.01	12	1594	32	0.84	<5	15	184	<5	0.08	<10	<10	201	<10	175	4
84509	0.3	2.28	62	41	0.7	<5	11.77	1	23	42	46	5.09	1	0.12	<10	1.81	2705	<2	0.01	13	1558	17	0.53	<5	18	218	<5	0.07	<10	<10	209	<10	120	4
84510	0.6	2.70	79	42	0.7	<5	10.91	5	27	41	80	5.44	<1	0.12	<10	2.34	2767	<2	0.01	13	1592	17	0.48	<5	18	187	<5	0.08	<10	<10	220	<10	447	4
84511	1.2	2.44	119	46	0.7	<5	10.60	5	30	37	102	5.12	<1	0.15	<10	2.02	2586	<2	0.01	12	1644	151	0.94	<5	16	185	<5	0.09	<10	<10	198	<10	352	4
84512	1.0	2.50	217	70	0.6	<5	6.81	8	27	44	101	5.67	<1	0.17	<10	1.97	2298	<2	0.01	14	1753	398	1.64	<5	13	106	<5	0.08	<10	<10	202	<10	512	4
84513	<0.2	2.65	62	48	0.8	<5	8.46	1	30	47	80	6.06	<1	0.09	<10	2.23	2366	<2	0.02	14	1861	20	1.37	<5	22	146	<5	0.12	<10	<10	279	<10	129	5
84514	<0.2	2.55	44	36	1.0	<5	11.09	8	22	47	16	4.97	<1	0.08	<10	2.28	2143	<2	0.01	13	1547	438	0.20	<5	20	198	<5	0.15	<10	<10	220	11	722	7
84515	0.2	2.57	1818	59	0.8	<5	8.25	30	31	40	74	5.47	<1	0.07	<10	2.46	2652	<2	0.02	13	1809	67	1.13	21	10	172	<5	0.10	<10	<10	207	<10	192	6
84516	<0.2	2.66	64	52	0.6	<5	5.33	3	28	59	58	5.86	<1	0.06	<10	2.29	2648	<2	0.01	14	1291	61	1.00	<5	15	96	<5	0.12	<10	<10	225	<10	336	6
84517	0.4	2.87	94	50	0.6	<5	5.89	11	30	54	87	6.47	<1	0.04	<10	2.59	2731	<2	0.02	14	1286	666	1.58	<5	19	109	<5	0.09	<10	<10	263	<10	1112	5
84518	<0.2	3.11	496	55	<0.5	<5	4.57	7	29	49	90	7.01	<1	0.04	<10	2.86	2835	<2	0.01	14	1356	209	1.72	10	21	88	<5	0.04	<10	<10	275	<10	773	4
84519	1.7	1.98	1326	121	<0.5	<5	10.46	56	25	37	561	6.03	<1	0.16	<10	1.85	3713	<2	0.01	14	1014	1382	1.39	18	16	293	<5	0.01	<10	<10	141	<10	5842	3
84520	<0.2	2.51	114	83	0.6	<5	7.06	7	28	49	99	6.25	1	0.07	<10	2.16	2903	<2	0.01	13	1311	179	1.68	<5	20	137	<5	0.08	<10	<10	246	<10	771	6
84521	<0.2	2.76	181	54	0.5	<5	6.66	10	28	58	91	6.56	1	0.05	<10	2.41	2714	<2	0.01	14	1299	216	1.58	<5	20	123	<5	0.08	<10	<10	255	<10	1083	5
84522	<0.2	2.95	68	51	0.6	<5	5.19	5	34	56	96	7.01	<1	0.03	<10	2.69	2569	<2	0.02	16	1352	71	1.96	<5	21	91	<5	0.13	<10	<10	291	<10	635	6
84523	<0.2	2.75	46	50	0.7	<5	6.28	3	30	51	87	6.74	<1	0.04	<10	2.46	2577	<2	0.02	14	1390	33	1.76	<5	17	108	<5	0.14	<10	<10	259	<10	355	7
84524	<0.2	2.35	62	51	0.8	<5	9.58	1	24	44	90	5.70	1	0.06	<10	2.01	3536	<2	0.01	13	1182	18	1.25	<5	16	165	<5	0.11	<10	<10	226	<10	102	6
84525	>200.0	0.81	1854	136	<0.5	58	4.43	1	60	22	2464	3.08	1	0.08	<10	0.24	855	131	0.05	23	910	393	0.66	346	2	144	5	0.03	<10	<10	22	17	292	7
84526	<0.2	2.47	69	62	0.9	<5	12.02	2	25	44	70	5.19	1	0.07	<10	2.09	3784	<2	0.01	12	1138	88	0.60	<5	15	183	5	0.13	<10	<10	201	<10	220	6
84527	<0.2	2.56	84	74	0.7	<5	7.19	2	31	44	75	6.20	<1	0.04	<10	2.39	2789	<2	0.01	13	1313	15	1.81	<5	14	119	<5	0.15	<10	<10	240	<10	268	7
84528	0.2	2.17	54	158	0.6	<5	6.46	1	32	51	79	5.95	<1	0.04	<10	1.99	2151	<2	0.02	14	1317	23	2.18	<5	10	123	<5	0.15	<10	<10	206	<10	192	7
84529	0.5	2.70	49	155	<0.5	<5	5.98	1	31	52	94	6.85	1	0.06	<10	2.57	2120	<2	0.01	13	1398	27	2.20	<5	20	125	<5	0.05	<10	<10	260	<10	100	5
84530	<0.2	2.71	96	61	0.5	<5	9.85	<1	21	43	53	5.55	1	0.10	<10	2.29	2356	<2	0.01	12	1235	41	0.54	<5	18	197	5	0.04	<10	<10	205	<10	48	4
84531	1.4	1.37	1069	102	<0.5	<5	8.14	2	26	45	135	5.31	<1	0.28	<10	1.24	2479	<2	0.01	12	1135	90	2.17	16	9	304	<5	<0.01	<10	<10	93	<10	256	3
84532	0.6	2.70	137	66	<0.5	<5	6.50	6	29	36	84	6.12	<1	0.23	<10	2.10	3021	<2	<0.01	14	1392	48	1.18	6	11	120	<5	<0.01	<10	<10	163	<10	688	3
84533	1.5	1.15	200	96	<0.5	<5	7.35	3	27	30	79	4.98	<1	0.29	<10	1.41	2452	<2	0.01	12	1249	43	1.46	7	9	183	<5	<0.01	<10	<10	88	<10	368	3
139064	18.8	0.17	620	<10	<0.5	10	0.11	55	7	57	779	14.19	<1	0.11	<10	0.08	86	3	<0.01	1	359	9573	>5.00	15	<1	4	<5	0.01	<10	38	30	<10	7284	8

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2596RJ

Date : Aug-06-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 11

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139065	23.7	0.33	640	<10	<0.5	9	0.11	54	8	107	784	13.85	<1	0.10	<10	0.21	370	10	0.01	2	396	9900	>5.00	17	1	5	<5	0.01	<10	<10	44	<10	7169	9
139066	12.8	0.12	625	45	<0.5	17	<0.01	14	5	54	263	>15.00	<1	0.19	<10	0.04	169	5	<0.01	<1	574	6453	4.00	14	<1	2	<5	0.04	<10	35	76	<10	1708	13
139067	5.8	0.55	455	48	<0.5	<5	0.05	6	7	107	95	8.87	<1	0.21	<10	0.28	790	37	0.01	2	655	2722	4.41	7	2	6	<5	0.05	<10	<10	54	<10	965	5
139068	2.8	0.78	120	115	<0.5	<5	1.04	14	7	82	154	2.95	<1	0.20	<10	0.51	2174	<2	<0.01	2	623	1077	1.29	<5	1	26	<5	<0.01	<10	<10	26	<10	1996	3
139069	3.4	0.54	156	152	<0.5	<5	0.29	5	9	153	130	2.93	<1	0.17	<10	0.33	1564	2	0.01	4	451	1312	1.31	<5	1	9	<5	<0.01	<10	<10	20	<10	934	3
139070	16.5	0.52	1188	114	<0.5	<5	1.35	54	9	100	997	4.25	<1	0.18	<10	0.30	1715	<2	0.01	3	684	5188	2.52	5	1	24	<5	<0.01	<10	<10	18	79	6437	3
139071	16.5	0.77	202	138	<0.5	<5	1.18	53	7	165	352	3.58	1	0.25	<10	0.46	2230	3	0.01	5	780	7969	2.11	7	2	49	<5	<0.01	<10	<10	23	96	7763	4
139072	36.5	0.25	5068	42	<0.5	<5	0.92	166	15	154	2823	7.75	1	0.11	<10	0.13	1104	<2	0.01	4	497	9900	>5.00	13	<1	15	<5	<0.01	<10	<10	8	176	>10000	4
139073	0.6	1.02	85	125	<0.5	<5	1.28	2	8	102	15	3.30	<1	0.31	10	0.65	2011	2	0.01	3	931	136	1.37	<5	2	33	<5	<0.01	<10	<10	27	<10	171	3
139074	0.6	0.92	109	102	<0.5	<5	2.03	2	8	56	15	3.27	<1	0.26	<10	0.62	1999	<2	0.01	2	938	164	1.51	<5	2	49	<5	<0.01	<10	<10	28	<10	127	3
139075	0.5	0.74	86	122	<0.5	<5	1.40	4	7	77	14	2.98	<1	0.27	<10	0.42	1699	2	0.01	2	856	67	1.29	<5	2	36	<5	<0.01	<10	<10	24	<10	471	3
139076	2.3	0.75	133	114	<0.5	<5	1.52	16	7	66	77	3.39	<1	0.27	<10	0.45	1598	2	0.01	2	890	1244	1.99	<5	2	47	<5	<0.01	<10	<10	21	23	1838	3
139077	5.2	0.86	360	76	<0.5	<5	1.14	26	8	143	230	5.72	<1	0.34	<10	0.49	1743	13	0.01	3	860	2730	4.47	<5	1	32	<5	<0.01	<10	<10	15	32	2636	4
139078	1.5	1.26	134	149	<0.5	<5	5.17	5	9	34	41	4.72	<1	0.30	11	0.79	3697	<2	0.01	1	1247	287	2.26	<5	2	77	<5	<0.01	<10	<10	30	<10	517	3
139079	0.6	0.96	105	178	<0.5	<5	0.68	5	7	36	39	3.15	<1	0.34	16	0.43	2189	<2	0.01	1	1090	151	0.76	<5	2	12	<5	<0.01	<10	<10	20	<10	401	2
139080	0.6	0.94	77	167	<0.5	<5	0.99	4	11	30	32	3.99	<1	0.34	16	0.45	2330	<2	0.01	2	1172	102	1.59	<5	2	25	<5	<0.01	<10	<10	19	<10	352	2
139081	0.7	1.20	105	201	<0.5	<5	0.40	3	12	54	23	5.03	<1	0.37	15	0.62	1933	12	0.01	2	1370	137	1.82	<5	2	8	<5	<0.01	<10	<10	21	<10	265	3
139082	0.8	1.41	71	185	<0.5	<5	0.56	2	13	32	17	5.02	<1	0.33	14	0.70	2805	8	0.01	1	1335	45	1.43	<5	2	13	<5	<0.01	<10	<10	26	<10	182	3
139083	<0.2	0.94	41	266	<0.5	<5	2.15	2	8	65	9	3.82	<1	0.23	<10	0.53	1400	<2	0.01	2	1044	74	0.34	<5	3	47	<5	<0.01	<10	<10	28	<10	237	3
139084	0.2	0.58	46	364	0.5	<5	2.56	2	9	41	10	3.64	<1	0.22	<10	0.41	1432	<2	0.01	2	1139	118	0.43	<5	2	60	<5	<0.01	<10	<10	19	<10	225	2
139085	0.3	0.65	58	155	0.5	<5	2.06	4	10	68	17	3.77	<1	0.26	10	0.29	1324	4	0.01	2	1212	183	0.57	<5	3	29	<5	<0.01	<10	<10	22	<10	417	3
139086	0.7	0.95	63	113	<0.5	<5	3.19	8	10	43	46	3.80	<1	0.23	<10	0.65	1512	<2	0.01	2	1146	755	0.58	<5	3	79	<5	<0.01	<10	<10	35	10	759	3
139087	0.2	0.79	48	361	0.5	<5	3.52	4	9	45	12	4.05	<1	0.27	<10	0.61	1637	2	0.02	2	1179	71	0.51	<5	3	111	<5	<0.01	<10	<10	27	<10	424	3
139088	0.5	0.59	88	461	<0.5	<5	4.52	14	9	46	18	4.00	<1	0.26	<10	0.45	1758	2	0.01	2	1235	195	0.63	<5	3	123	<5	<0.01	<10	<10	22	12	921	3
139089	0.2	0.50	253	439	<0.5	<5	2.90	6	9	71	8	3.77	<1	0.27	<10	0.20	1324	3	0.01	3	1160	120	0.34	<5	3	45	<5	<0.01	<10	<10	19	<10	435	3
139090	0.5	0.64	500	227	<0.5	<5	1.82	24	12	67	32	4.18	<1	0.23	<10	0.46	1545	2	0.01	5	1230	319	0.34	<5	4	41	<5	<0.01	<10	<10	35	19	1555	3
139091	1.5	0.39	222	431	<0.5	<5	1.60	41	11	62	103	4.15	<1	0.27	<10	0.15	1407	3	0.01	2	1190	1254	0.66	<5	3	28	<5	<0.01	<10	<10	17	47	3856	3
139092	7.4	0.84	445	168	<0.5	<5	1.76	92	11	92	325	4.60	<1	0.27	<10	0.58	1600	2	0.01	2	1058	6264	1.48	<5	3	42	<5	<0.01	<10	<10	26	116	8200	3
139093	7.9	1.36	312	137	<0.5	<5	1.37	94	13	53	182	5.26	<1	0.25	<10	0.81	1603	<2	0.02	2	1306	7520	1.67	<5	3	39	<5	<0.01	<10	<10	47	117	8300	3
139094	9.6	0.56	344	85	<0.5	<5	0.80	1	8	43	15	4.14	1	0.31	<10	0.24	421	3	<0.01	33	879	87	3.32	28	2	25	<5	<0.01	<10	<10	21	<10	117	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2596RJ**

Date : Aug-06-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 11

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139095	>200.0	0.24	1360	18	<0.5	<5	0.23	73	5	195	173	8.62	4	0.20	<10	0.06	275	<2	<0.01	10	490	5314	>5.00	264	<1	8	<5	<0.01	<10	<10	13	<10	>10000	5
139096	86.7	0.73	483	166	<0.5	<5	0.78	3	8	51	57	3.78	<1	0.30	<10	0.40	985	<2	0.01	3	906	609	1.52	27	2	27	<5	<0.01	<10	<10	27	<10	515	2
139097	5.8	0.72	73	168	<0.5	<5	1.30	<1	10	32	21	3.86	<1	0.34	<10	0.58	1210	<2	0.01	2	1081	51	0.95	<5	3	67	<5	<0.01	<10	<10	27	<10	112	2
139098	4.9	0.86	20	35	<0.5	<5	>15.00	<1	10	94	32	2.78	1	0.05	<10	0.85	1597	<2	0.01	9	502	24	0.33	6	11	597	8	<0.01	<10	<10	73	<10	66	2
139099	9.6	2.06	219	57	<0.5	<5	9.02	6	21	87	128	5.03	<1	0.09	<10	1.70	1853	<2	0.01	17	1159	442	0.68	7	13	316	6	0.01	<10	<10	157	<10	656	3
139100	0.5	2.53	102	79	<0.5	<5	3.22	1	30	120	129	6.46	<1	0.16	<10	1.98	1713	<2	0.02	23	1366	37	1.11	6	15	69	<5	0.01	<10	<10	201	<10	185	4
139101	26.8	1.44	>10000	32	<0.5	<5	4.42	1013	21	74	897	12.97	6	0.13	<10	1.06	1602	<2	0.01	16	986	8186	>5.00	131	8	92	<5	<0.01	<10	<10	108	<10	>10000	8
139102	0.5	1.89	180	40	<0.5	<5	11.38	1	17	74	96	4.80	<1	0.08	<10	1.43	3126	<2	0.01	17	957	32	0.83	7	12	203	6	<0.01	<10	<10	141	<10	209	3
139103	12.2	0.92	6741	28	<0.5	<5	3.88	671	19	37	300	9.08	5	0.07	<10	0.69	1898	<2	<0.01	13	641	3235	>5.00	71	6	80	<5	<0.01	<10	<10	79	<10	>10000	5
139104	58.7	2.04	3807	56	<0.5	<5	2.30	37	23	94	303	8.92	<1	0.14	<10	1.66	1282	<2	0.01	18	1154	>10000	>5.00	81	10	54	<5	<0.01	<10	<10	162	<10	4208	5
139105	3.4	1.86	728	188	0.6	<5	3.38	81	18	33	186	4.84	1	0.21	<10	1.66	1252	16	0.02	37	1074	533	1.80	10	5	92	5	0.11	<10	<10	88	<10	8758	4
139106	0.8	2.16	341	64	<0.5	<5	7.23	7	18	79	66	5.29	<1	0.16	<10	1.57	2758	<2	<0.01	17	1061	187	0.76	9	12	106	<5	0.01	<10	<10	142	<10	891	3
SD0807	35.2	0.45	381	107	<0.5	<5	0.35	8	6	57	28	3.25	<1	0.24	<10	0.15	166	2	0.01	3	665	247	2.49	25	1	9	<5	<0.01	<10	<10	13	<10	1221	2
SD0808	103.1	0.13	618	41	<0.5	<5	<0.01	31	4	179	420	9.94	8	0.05	<10	0.05	131	21	<0.01	5	234	>10000	3.69	30	<1	3	<5	<0.01	<10	21	26	<10	4681	6
SD0809	8.9	0.32	93	17	<0.5	<5	1.26	369	17	211	189	1.49	1	0.05	<10	0.24	842	33	0.01	9	265	957	1.89	16	3	82	<5	<0.01	<10	<10	14	<10	>10000	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 35 Years

Assay Certificate

8V-2615-RA1

Company: **Ascot Resources Ltd**
 Project:
 Attn: **Sue Deane**

Jul-24-08

We hereby certify the following assay of 14 core samples submitted Jul-21-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne	Pb %	Zn %
Snow #1	1.68	1.45	>200	2688	1.32	1.41
Snow #2	0.30		96.8		1.09	1.59
Ty#1 Ext	0.44		34.9		1.47	
Hole 7 #83762	3.51		>200	5160	2.58	6.20
Hole 22 #84979	2.46		21.2			
Hole 22 #84991	0.61		60.5			3.11
139103	2.00		42.9		1.21	16.1
PB08-01	0.65		43.8			
PB08-02	2.00		9.08			
PB08-03	0.57	0.58	6.74			
PB08-04	0.29		27.7			
PB08-05	0.10		13.3			
PB08-06	0.13		6.85			
SD08-10	0.90		67.4			
*0218	0.95					
*CCu-1c				130.0	0.35	3.94
*BLANK	<0.01			<0.1	<0.01	<0.01

Certified by _____



Assayers Canada
 8282 Sherbrooke St., Vancouver, B.C., V5X 4R6
 Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2615RJ

Date : Jul-24-08

Sample type :

Ascot Resources Ltd

Project :

Multi-Element ICP-AES Analysis

Attention : Sue Deane

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
Snow #1	>200.0	0.26	7806	44	<0.5	<5	0.19	84	3	266	833	2.68	2	0.08	<10	0.09	266	3	0.01	10	0.021	>10000	2.46	110	1	6	<5	<0.01	<10	<10	12	<10	>10000	2
Snow #2	96.8	0.11	240	49	<0.5	<5	0.86	84	7	109	666	4.13	2	0.08	<10	0.03	879	<2	0.01	4	0.022	>10000	4.69	28	<1	13	<5	<0.01	<10	<10	7	<10	>10000	2
Ty#1 Ext	34.9	0.07	663	10	<0.5	9	0.04	57	8	147	910	15.47	<1	0.08	<10	0.03	19	<2	0.01	7	0.042	>10000	>10.00	21	<1	3	<5	0.01	<10	34	26	<10	7411	9
Hole 7 #83762	>200.0	<0.01	2163	<10	<0.5	13	0.08	381	3	109	1478	21.36	11	0.04	<10	0.01	114	<2	0.01	7	0.036	>10000	>10.00	1277	<1	5	<5	<0.01	<10	37	23	<10	>10000	13
Hole 22 #84979	21.3	2.35	2290	14	<0.5	11	0.30	88	16	89	142	19.32	<1	0.25	<10	1.31	723	<2	0.01	6	0.058	1070	>10.00	18	4	21	<5	0.01	<10	<10	71	<10	8534	12
Hole 22 #84991	60.5	0.98	598	29	<0.5	<5	1.05	250	7	154	453	8.30	2	0.13	<10	0.90	2230	3	0.01	7	0.049	6235	9.08	33	1	36	<5	<0.01	<10	<10	31	<10	>10000	5
139103	42.9	0.12	>10000	11	<0.5	8	4.70	1494	26	32	771	17.81	9	0.01	<10	0.11	1235	<2	0.01	16	0.051	>10000	>10.00	186	2	86	<5	<0.01	<10	<10	30	<10	>10000	11
PB08-01	43.9	0.36	202	129	<0.5	<5	0.05	7	3	144	18	3.37	3	0.28	<10	0.04	28	<2	0.01	5	0.043	2630	2.05	14	1	5	<5	<0.01	<10	<10	10	<10	899	2
PB08-02	9.1	0.38	2483	133	<0.5	<5	0.04	3	1	31	7	2.08	<1	0.35	<10	0.03	28	<2	0.01	1	0.047	90	0.33	99	1	3	<5	<0.01	<10	<10	8	<10	354	1
PB08-03	6.7	0.53	436	197	<0.5	<5	0.06	2	2	24	15	4.66	<1	0.44	14	0.04	253	<2	0.01	1	0.081	141	0.23	26	1	3	<5	<0.01	<10	<10	10	<10	88	3
PB08-04	27.8	0.63	212	43	<0.5	<5	0.34	28	9	73	54	6.59	2	0.22	<10	0.35	574	<2	0.01	4	0.057	2097	5.96	23	1	19	<5	<0.01	<10	<10	23	<10	3509	4
PB08-05	13.4	0.14	144	13	<0.5	8	0.12	6	5	92	28	14.98	<1	0.15	<10	0.07	151	<2	0.01	3	0.019	132	>10.00	20	<1	15	<5	<0.01	<10	10	19	14	223	9
PB08-06	6.8	0.57	58	74	<0.5	<5	0.24	26	8	82	8	4.52	3	0.21	<10	0.42	1480	2	0.01	4	0.058	1443	3.39	10	1	21	<5	<0.01	<10	<10	19	<10	4567	3
SD08-10	67.4	0.16	107	82	<0.5	<5	0.01	3	2	83	27	3.87	5	0.13	<10	0.01	11	18	0.01	2	0.039	4561	1.87	52	1	3	<5	<0.01	<10	<10	10	<10	581	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Signed: 



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2631-RA1

Company: **Ascot Resources Ltd**
 Project:
 Attn:

Aug-19-08

We hereby certify the following assay of 20 core samples submitted Jul-22-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %	Zn %
48856	5.54	5.93	1152		2.47
48857	1.72		1152		1.42
48858	0.28				
48859	0.57				
83521	1.40		1483		1.01
83522	0.43				
83523	0.51		198.3		1.16
83524	1.97		613.0		
83525	0.17				
83635	0.60	0.61			
83636	1.07		1514		
83637	0.47				
83638	0.52				
83639	0.62				
83713	0.70				
83714	1.96		945.0		
83715	2.39		707.0	3.34	4.65
83716	1.41		812.0		1.34
83717	1.21		1090		1.07
83718	2.24	2.24	1432	1.00	3.49
*0218	0.91				
*CCu-1c			128.7	0.33	3.94
*BLANK	<0.01		<0.1	<0.01	<0.01

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2631RJ**

Date : Aug-19-08

Ascot Resources Ltd

Attention:

Project:

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
48856	>200.0	0.14	1205	29	<0.5	<5	1.11	192	5	124	798	8.38	5	0.11	41	0.05	443	5	0.01	7	287	9053	>5.00	130	<1	19	<0.01	<10	<10	13	<10	>10000	5
48857	>200.0	0.14	880	41	<0.5	<5	1.40	125	4	115	618	5.52	11	0.09	37	0.06	592	16	0.01	13	199	5712	>5.00	95	<1	21	<0.01	<10	<10	11	<10	>10000	3
48858	24.8	0.66	199	80	<0.5	<5	1.60	13	14	73	72	4.67	<1	0.25	<10	0.34	941	20	0.01	4	808	924	3.60	7	1	63	<0.01	<10	<10	31	<10	1724	3
48859	28.1	2.12	119	189	<0.5	<5	2.35	3	20	29	324	5.34	<1	0.42	10	1.24	1815	15	0.01	15	1407	66	1.02	6	3	95	<0.01	<10	<10	63	<10	422	3
83521	>200.0	0.11	1438	15	<0.5	5	0.14	69	6	89	517	9.42	3	0.11	18	0.04	165	6	0.01	3	268	5277	>5.00	191	<1	6	<0.01	<10	<10	13	<10	>10000	5
83522	55.6	0.17	755	80	<0.5	<5	0.57	6	6	124	99	4.68	<1	0.16	<10	0.10	441	9	0.01	4	311	396	4.21	31	<1	27	<0.01	<10	<10	9	<10	877	3
83523	>200.0	0.19	670	77	<0.5	<5	0.84	15	7	113	167	4.72	<1	0.14	<10	0.19	692	10	0.01	4	376	886	4.09	53	1	42	<0.01	<10	<10	13	<10	2264	3
83524	>200.0	0.28	850	32	<0.5	<5	1.63	95	12	87	627	8.90	2	0.15	<10	0.17	910	13	0.01	5	465	4661	>5.00	97	1	71	<0.01	<10	<10	28	<10	>10000	5
83525	35.5	1.34	197	115	0.5	<5	10.91	3	18	18	376	4.15	<1	0.27	11	0.73	3613	50	0.01	45	956	82	2.01	<5	4	363	0.01	<10	<10	58	<10	431	3
83635	184.9	1.32	1700	65	<0.5	<5	5.12	50	31	239	759	6.85	1	0.07	<10	0.78	2618	50	0.02	40	1377	8351	4.44	46	11	104	0.06	<10	<10	142	<10	8904	6
83636	>200.0	1.17	>10000	76	<0.5	<5	3.42	28	31	249	499	6.58	<1	0.10	<10	0.67	1706	60	0.01	38	1504	3996	3.85	366	12	66	0.05	<10	<10	163	<10	5936	5
83637	31.1	1.13	6165	44	<0.5	<5	5.96	16	29	227	276	6.26	<1	0.07	<10	0.59	2157	90	0.01	31	1156	769	3.72	106	11	82	0.04	<10	<10	142	<10	3338	5
83638	25.2	1.76	361	67	0.5	<5	4.82	4	29	184	194	5.41	<1	0.07	<10	1.12	2138	97	0.03	26	1639	123	0.97	9	9	137	0.10	<10	<10	122	<10	690	10
83639	8.1	1.15	78	36	<0.5	<5	6.66	2	19	83	666	3.02	<1	0.07	<10	0.77	1689	115	0.01	14	1235	25	0.19	<5	6	130	0.07	<10	<10	74	<10	297	7
83713	25.7	0.25	2829	82	<0.5	<5	0.15	4	6	105	27	5.06	1	0.14	<10	0.07	175	<2	0.01	4	330	209	4.52	59	<1	7	<0.01	<10	<10	11	<10	487	3
83714	>200.0	0.18	813	71	<0.5	<5	0.17	41	5	107	358	5.72	1	0.11	<10	0.06	166	3	0.01	3	317	3733	>5.00	145	<1	6	<0.01	<10	<10	12	<10	6754	3
83715	>200.0	<0.01	1689	12	<0.5	10	0.01	349	4	100	1571	>15.00	7	0.03	26	0.01	14	<2	0.01	22	301	>10000	>5.00	980	<1	1	<0.01	<10	55	20	<10	>10000	10
83716	>200.0	0.10	1528	16	<0.5	7	0.05	102	6	138	363	11.46	2	0.09	15	0.03	110	<2	0.01	22	229	5258	>5.00	144	<1	3	<0.01	<10	37	16	<10	>10000	7
83717	>200.0	0.42	849	27	<0.5	<5	0.13	81	7	116	568	8.72	2	0.17	<10	0.17	539	<2	0.01	89	578	5153	>5.00	102	<1	5	<0.01	<10	<10	21	<10	>10000	5
83718	>200.0	<0.01	2003	11	<0.5	11	0.01	271	7	190	332	>15.00	5	0.04	11	0.01	83	<2	0.01	4	259	>10000	>5.00	271	<1	1	<0.01	<10	48	23	<10	>10000	10

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Quality Assaying for over 25 Years

Assay Certificate

8V-2690-RA1

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 12**
Attn: **Sue Deane**

Aug-13-08

We hereby certify the following assay of 24 core samples submitted Jul-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84422	0.01	<0.01	<0.1
84423	0.02		<0.1
84424	0.01		0.2
84425	0.45		0.3
84426	0.02		<0.1
84427	0.01		0.2
84428	0.02		<0.1
84429	0.01		0.2
84430	0.01		<0.1
84431	0.07	0.05	0.4
84432	0.02		<0.1
84433	0.01		0.2
84434	0.02		<0.1
84435	0.02		<0.1
84436	0.01		<0.1
84437	<0.01		<0.1
84438	<0.01		<0.1
84439	0.18		4.8
84440	0.11		<0.1
84441	0.87	0.80	3.3
84442	0.02		0.1
84443	0.02		1.2
84444	0.01		0.4
84445	0.02		<0.1
*0218	0.90		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2690-RA2

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 12**
Attn: **Sue Deane**

Aug-13-08

We hereby certify the following assay of 24 core samples submitted Jul-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84446	0.03	0.03	1.0
84447	0.02		1.4
84448	0.04		0.6
84449	0.02		0.5
84450	<0.01		<0.1
84451	0.11		1.3
84452	0.19		2.0
84453	0.07		1.4
84454	0.07		1.1
84455	0.02	0.01	0.8
84456	0.05		0.6
84457	0.09		1.7
84458	0.04		0.3
84459	0.01		0.5
84460	0.04		0.8
84461	0.58		4.0
84462	0.37		5.1
84463	0.02		0.6
84464	0.02		0.8
84465	0.01	0.02	<0.1
84466	0.01		0.3
84467	0.01		0.6
84468	0.01		0.4
84469	<0.01		0.4
*0218	0.94		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2690-RA3

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 12**
Attn: **Sue Deane**

Aug-13-08

We hereby certify the following assay of 24 core samples submitted Jul-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84470	0.01	0.03	<0.1
84471	<0.01		<0.1
84472	<0.01		<0.1
84473	0.01		0.4
84474	0.01		<0.1
84475	6.26		2.9
84476	0.02		0.1
84477	0.01		<0.1
84478	0.01		0.6
84479	0.03	0.04	1.3
84480	0.07		<0.1
84481	0.02		0.1
84482	0.03		0.5
84483	0.58		12.7
84484	0.02		0.7
84485	0.02		0.6
84486	0.01		0.2
84487	0.01		0.1
84488	0.01		<0.1
84489	0.01	0.01	<0.1
84490	0.02		<0.1
84491	0.01		<0.1
84492	0.01		<0.1
84493	0.02		0.2
*0218	0.88		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2690-RA4

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 12**
Attn: **Sue Deane**

Aug-13-08

We hereby certify the following assay of 24 core samples submitted Jul-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84534	0.01	0.02	<0.1
84535	0.09		0.3
84536	0.16		0.2
84537	0.04		0.8
84538	0.03		3.3
84539	0.08		<0.1
84540	0.01		<0.1
84541	0.01		0.6
84542	0.02		<0.1
84543	<0.01	0.01	<0.1
84544	<0.01		<0.1
84545	<0.01		<0.1
84546	<0.01		<0.1
84547	0.01		<0.1
84548	0.01		<0.1
84549	0.02		<0.1
84550	<0.01		<0.1
84551	0.10		1.5
84552	0.01		0.5
84553	0.02	0.02	<0.1
84554	<0.01		<0.1
84555	0.01		<0.1
84556	<0.01		0.5
84557	<0.01		1.0
*0218	0.89		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2690-RA5

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 12**
Attn: **Sue Deane**

Aug-13-08

We hereby certify the following assay of 24 core samples submitted Jul-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84558	0.01	0.02	0.5
84559	<0.01		<0.1
84560	0.01		0.7
84561	<0.01		1.0
84562	0.02		2.2
84563	0.05		2.4
84564	0.03		<0.1
84565	0.01		<0.1
84566	0.01		<0.1
84567	0.02	0.03	0.7
84568	0.04		0.5
84569	0.01		0.3
84570	0.03		0.7
84571	0.01		<0.1
84572	0.01		<0.1
84573	0.02		0.2
84574	<0.01		<0.1
84575	0.03		<0.1
84575 A	<0.01		<0.1
84576	0.05	0.06	0.8
84577	0.04		0.7
84578	0.05		1.3
84579	0.06		0.9
84580	0.07		3.3
*0218	0.87		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2690-RA6

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 12**
Attn: **Sue Deane**

Aug-13-08

We hereby certify the following assay of 24 core samples submitted Jul-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84581	0.07	0.04	0.5
84582	0.10		1.6
84583	0.12		35.1
84584	0.16		4.5
84585	0.08		1.4
84586	0.06		1.4
84587	0.03		1.2
84588	0.07		1.9
84589	0.11		2.7
84590	0.08	0.09	2.1
84591	0.11		2.1
84592	0.05		1.5
84593	0.09		1.0
84594	0.04		0.5
84595	0.03		0.9
84596	0.08		1.4
84597	0.03		0.7
84598	0.03		0.5
84599	0.03		0.3
84600	1.42	1.69	155
84601	0.01		0.8
84602	0.01		1.0
84603	0.02		0.8
84604	0.01		<0.1
*0218	0.88		
*CCu-1c			
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2690-RA7

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 12**
Attn: **Sue Deane**

Aug-13-08

We hereby certify the following assay of 24 core samples submitted Jul-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84605	0.03	0.02	0.2
84606	0.03		0.4
84607	0.02		<0.1
84608	0.02		<0.1
84609	0.03		<0.1
84610	0.04		<0.1
84611	0.03		0.2
84612	0.05		1.0
84613	0.02		0.2
84614	<0.01	<0.01	<0.1
84615	0.01		0.6
84616	0.04		0.1
84617	0.18		0.5
84618	0.05		0.4
84619	0.03		0.4
84620	<0.01		0.3
84621	0.05		<0.1
84622	<0.01		0.2
84623	<0.01		<0.1
84624	<0.01	0.01	0.2
84625	<0.01		<0.1
84626	<0.01		<0.1
84627	0.05		0.3
84628	<0.01		<0.1
*0218	0.91		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2690-RA8

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 12**
Attn: **Sue Deane**

Aug-13-08

We hereby certify the following assay of 24 core samples submitted Jul-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84629	0.01	<0.01	0.7
84630	0.75		2.7
84631	0.03		1.8
84632	0.03		1.3
84633	0.02		0.2
84634	0.03		0.3
84635	0.01		0.4
84636	0.05		7.0
84637	0.01		0.4
84638	0.03	0.01	1.3
84639	0.01		<0.1
84640	0.01		1.2
84641	0.01		0.8
84642	<0.01		0.7
84643	0.01		2.2
84644	0.01		0.8
84645	<0.01		0.6
84646	0.01		<0.1
84647	0.01		0.2
84648	0.01	0.03	0.5
84649	0.15		1.9
84650	1.68		174
84651	0.01		0.9
84652	0.11		3.6
*0218	0.89		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2690-RA9

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 12**
Attn: **Sue Deane**

Aug-13-08

We hereby certify the following assay of 24 core samples submitted Jul-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84653	0.06	0.05	4.0
84654	0.14		1.7
84655	0.04		0.4
84655 A	0.02		<0.1
84656	0.02		<0.1
84657	0.01		<0.1
84658	0.02		0.2
84659	0.02		<0.1
84660	0.01		<0.1
84661	0.01	0.01	<0.1
84662	0.01		0.2
84663	0.03		3.1
84664	0.02		1.8
84665	0.02		0.5
84666	0.03		0.3
84667	0.02		0.3
84668	0.02		0.2
84669	0.01		1.7
84670	0.02		<0.1
84671	0.03	0.02	8.0
84672	0.02		14.7
84673	0.02		2.3
84674	0.01		<0.1
84675	0.01		<0.1
*0218	0.88		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2690-RA10

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 12**
Attn: **Sue Deane**

Aug-13-08

We hereby certify the following assay of 24 core samples submitted Jul-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84676	0.02	<0.01	1.5
84677	0.03		3.3
84678	0.02		0.7
84679	0.02		1.0
84680	0.02		1.1
84681	0.02		0.3
84682	0.02		0.8
84683	0.03		0.1
84684	0.03		<0.1
84685	0.03	0.02	<0.1
84686	0.01		0.4
84687	0.02		<0.1
84688	0.02		0.2
84770	0.05		0.4
84771	0.10		1.2
84772	0.04		0.4
84773	0.07		0.4
84774	0.13		0.2
84775	<0.01		<0.1
84776	0.09	0.09	0.3
84777	0.09		0.5
84778	0.11		0.3
84779	0.08		0.3
84780	0.04		0.2
*0218	0.88		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2690-RA11

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 12**
Attn: **Sue Deane**

Aug-13-08

We hereby certify the following assay of 24 core samples submitted Jul-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84781	0.04	0.03	0.6
84782	0.06		0.3
84783	0.06		0.2
84784	0.05		0.1
84785	0.03		0.2
84786	0.20		2.3
84787	0.12		1.5
84788	0.05		0.3
84789	0.36		1.2
84790	0.10	0.08	0.6
84791	0.03		0.7
84792	0.07		0.8
84793	0.05		0.3
139107	0.21		2.9
139108	0.01		<0.1
139109	0.01		<0.1
139110	<0.01		<0.1
139111	0.01		<0.1
139112	0.03		0.2
139113	0.01	0.02	<0.1
139114	0.01		<0.1
139115	0.39		8.7
139116	0.51		11.1
139117	0.41		13.4
*0218	0.95		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2690-RA12

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 12**
Attn: **Sue Deane**

Aug-13-08

We hereby certify the following assay of 24 core samples submitted Jul-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %
139118	0.42	0.44	9.4	
139119	0.28		4.4	
139120	0.29		5.4	
139121	0.66		16.5	
139122	2.15		40.2	
139123	0.74		51.0	
139124	3.09		96.9	1.36
139125	2.51		45.0	
139126	5.99		115	1.04
139127	0.18	0.17	2.6	
139128	0.18		4.8	
139129	0.29		5.5	
139130	0.17		4.4	
139131	0.13		4.2	
139132	0.04		1.9	
139133	0.13		7.1	
139134	0.04		2.0	
139135	0.08		3.0	
139136	0.04		2.1	
139137	0.24	0.24	2.9	
139138	0.12		3.1	
139139	0.27		3.6	
139140	0.02		10.7	
139141	0.01		0.5	
*0218	0.98			
*CCu-1c				0.33
*BLANK	<0.01			<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2690-RA13

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 12**
Attn: **Sue Deane**

Aug-13-08

We hereby certify the following assay of 24 core samples submitted Jul-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne	Pb %	Zn %
139142	0.02	0.02	0.8			
139143	<0.01		1.3			
139144	0.02		0.7			
139145	0.02		0.8			
139146	0.02		0.2			
139147	<0.01		0.2			
139148	0.25		4.5			
139149	0.38		4.0			
139150	0.28		3.5			
139151	0.56	0.56	9.2			
139152	0.23		3.9			
139153	0.20		2.0			
139154	1.03		>200	240.4		
139155	0.74		42.4			
139156	0.58		42.0			
139157	0.04		2.6			
139158	0.17		5.7			
139159	1.17		128			
139160	7.62		>200	475.2	1.24	1.26
139161	0.95	0.92	>200	269.5		
139162	0.74		>200	206.7		
139163	0.21		6.9			
139164	0.35		5.3			
139165	0.20		12.7			
*0218	0.89					
*CCu-1c				128.4	0.33	3.97
*BLANK	<0.01			<0.1	<0.01	<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2690-RA14

Company: **Ascot Resources Ltd.**
 Project: **Dilworth/Shipment 12**
 Attn: **Sue Deane**

Aug-13-08

We hereby certify the following assay of 6 core samples submitted Jul-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
139166	0.34	0.38	6.4
139167	0.24		4.3
139168	0.20		3.0
139169	0.59		132
139170	0.10		34.1
*0218	0.85		
*BLANK	<0.01		

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2690RJ**

Date : Aug-13-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth/Shipment 12

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84422	<0.2	2.61	130	52	0.7	<5	9.43	2	24	42	74	5.36	1	0.12	<10	2.14	2761	<2	0.01	13	1196	38	0.66	<5	14	202	<5	0.09	<10	<10	185	<10	170	4
84423	<0.2	2.39	133	65	0.5	<5	10.69	3	21	37	80	5.13	1	0.10	<10	2.01	3087	<2	0.01	12	1189	4	0.74	<5	14	170	<5	0.07	<10	<10	189	<10	197	4
84424	0.2	3.18	81	46	<0.5	<5	7.27	2	30	43	104	7.37	1	0.14	<10	2.61	3153	<2	0.02	17	1518	13	1.49	6	14	171	<5	0.02	<10	<10	227	<10	52	5
84425	0.3	1.09	6756	21	<0.5	19	6.43	1	197	12	78	4.13	<1	0.05	13	0.26	767	16	0.09	35	1254	11	1.39	5	1	101	<5	0.05	<10	<10	43	<10	87	11
84426	<0.2	2.18	72	46	<0.5	<5	7.48	1	27	38	65	4.73	1	0.18	<10	1.64	2773	<2	0.01	14	1321	2	0.61	<5	10	140	<5	0.03	<10	<10	146	<10	43	3
84427	0.2	2.42	62	47	0.5	<5	8.54	1	28	36	82	5.78	1	0.19	<10	1.80	2831	<2	0.01	14	1402	6	1.25	5	10	158	<5	0.05	<10	<10	166	<10	32	4
84428	<0.2	2.27	73	59	<0.5	<5	6.60	2	27	34	82	5.86	<1	0.19	<10	2.17	2786	<2	0.01	15	1363	13	1.12	5	10	152	<5	0.02	<10	<10	151	<10	81	4
84429	0.2	2.94	112	60	0.5	<5	6.51	2	31	39	92	6.30	1	0.19	<10	2.39	3013	<2	0.01	16	1377	28	1.30	<5	11	148	<5	0.08	<10	<10	175	<10	87	4
84430	<0.2	3.15	92	54	0.6	<5	7.51	2	30	35	65	6.69	1	0.19	<10	2.39	3366	<2	0.01	15	1371	27	0.96	<5	10	156	<5	0.10	<10	<10	168	<10	85	4
84431	0.4	2.12	180	51	<0.5	<5	10.09	25	23	28	193	5.83	<1	0.19	<10	1.40	3042	<2	0.01	10	1004	100	2.01	<5	7	179	5	0.07	<10	<10	111	<10	2468	4
84432	<0.2	2.91	97	63	0.8	<5	9.67	3	27	30	62	6.10	1	0.19	<10	2.17	3188	<2	0.01	14	1272	12	0.90	<5	11	172	<5	0.13	<10	<10	159	<10	183	5
84433	0.2	2.67	83	61	0.8	<5	8.40	5	29	28	84	5.93	1	0.22	<10	2.03	2793	<2	0.01	13	1338	29	1.11	<5	10	144	5	0.13	<10	<10	149	<10	450	5
84434	<0.2	2.70	70	56	0.7	<5	10.46	2	28	29	57	5.43	1	0.21	<10	2.14	3366	<2	0.01	13	1266	16	0.60	<5	10	182	<5	0.10	<10	<10	140	<10	72	4
84435	<0.2	2.16	48	58	0.7	<5	11.25	1	24	31	13	4.47	1	0.39	<10	1.46	3027	<2	0.01	11	1025	5	0.67	<5	6	177	5	0.07	<10	<10	75	<10	38	4
84436	<0.2	2.98	117	50	0.7	<5	10.20	2	28	38	58	6.00	1	0.22	<10	2.35	3170	<2	0.01	15	1289	13	0.57	<5	12	162	<5	0.09	<10	<10	164	<10	76	5
84437	<0.2	2.61	117	44	0.5	<5	10.03	3	27	35	64	5.73	1	0.18	<10	2.12	2867	<2	0.01	14	1208	14	0.97	5	11	149	<5	0.08	<10	<10	153	<10	159	4
84438	<0.2	2.60	80	49	0.5	<5	11.05	1	24	35	54	5.18	1	0.16	<10	2.11	3345	<2	0.01	13	1186	9	0.39	<5	12	157	<5	0.07	<10	<10	163	<10	50	4
84439	4.8	1.57	2060	71	<0.5	<5	10.14	40	24	32	509	5.73	1	0.21	<10	1.85	3165	<2	0.01	13	1023	3240	1.39	16	11	395	<5	0.01	<10	<10	97	<10	4296	3
84440	<0.2	2.90	843	56	0.6	<5	9.26	16	29	42	60	6.26	1	0.16	<10	2.24	3786	<2	0.01	16	1278	87	0.88	5	14	144	<5	0.09	<10	<10	190	<10	1688	4
84441	3.3	2.37	2232	60	0.5	<5	5.18	23	29	40	187	6.63	1	0.17	<10	1.71	3071	<2	0.01	15	1267	707	2.35	15	10	77	<5	0.07	<10	<10	160	<10	2710	4
84442	<0.2	2.62	116	51	0.7	<5	9.20	2	26	40	64	6.03	1	0.12	<10	2.10	3110	<2	0.01	14	1257	71	0.63	<5	16	102	<5	0.09	<10	<10	211	<10	160	5
84443	1.2	2.97	84	48	0.8	<5	6.93	3	29	41	108	6.62	1	0.10	<10	2.47	2853	<2	0.01	15	1369	39	1.04	5	13	88	<5	0.10	<10	<10	220	<10	147	5
84444	0.4	3.16	59	48	0.8	<5	8.84	3	30	44	75	7.03	1	0.07	<10	2.58	3148	<2	0.01	15	1421	34	0.70	<5	14	110	<5	0.11	<10	<10	243	<10	199	6
84445	<0.2	2.45	62	73	0.7	<5	9.56	2	27	34	67	5.53	1	0.08	<10	1.95	2776	<2	0.01	13	1231	16	0.43	<5	14	123	<5	0.10	<10	<10	196	<10	66	6
84446	1.0	2.62	73	69	0.7	<5	9.39	2	25	38	77	5.56	1	0.19	<10	2.01	2783	<2	0.01	12	1532	53	0.59	<5	12	166	<5	0.09	<10	<10	151	<10	236	4
84447	1.4	1.52	164	76	<0.5	<5	11.63	5	22	32	40	5.26	<1	0.20	<10	1.54	3749	<2	0.01	46	1350	31	1.06	<5	8	262	<5	0.01	<10	<10	84	<10	338	2
84448	0.6	2.60	133	53	0.5	<5	9.67	27	24	34	94	5.86	1	0.15	<10	2.06	3494	<2	0.01	13	1492	180	0.97	<5	9	195	<5	0.07	<10	<10	138	32	2609	3
84449	0.5	2.31	185	57	0.7	<5	9.38	3	26	35	86	5.25	<1	0.19	<10	1.75	2988	<2	0.01	14	1606	25	0.97	<5	9	199	<5	0.11	<10	<10	140	<10	156	3
84450	<0.2	0.88	<5	246	0.7	<5	0.51	<1	8	93	1	2.13	<1	0.47	<10	0.60	597	<2	0.05	7	782	7	0.01	<5	2	38	<5	0.13	<10	<10	39	<10	72	2
84451	1.3	2.84	2575	68	0.7	<5	5.22	47	29	33	116	7.00	<1	0.24	<10	2.09	2983	<2	0.01	22	1772	240	1.53	5	9	99	<5	0.12	<10	<10	157	13	965	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2690RJ**

Date : Aug-13-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth/Shipment 12

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84452	2.0	1.85	1541	65	0.6	<5	7.98	24	28	36	166	7.53	<1	0.29	<10	1.12	2731	<2	0.01	17	1568	245	3.69	5	7	129	<5	0.10	<10	<10	99	<10	171	4
84453	1.4	2.39	312	67	0.9	<5	7.71	4	30	30	83	6.26	<1	0.25	<10	1.70	3364	<2	0.01	27	1799	60	1.79	7	9	155	<5	0.16	<10	<10	125	<10	76	4
84454	1.1	2.09	207	48	0.8	<5	9.80	3	24	37	67	4.94	<1	0.21	<10	1.56	3302	<2	0.01	21	1403	14	1.07	<5	7	183	<5	0.13	<10	<10	87	<10	51	3
84455	0.8	2.32	650	53	0.7	<5	8.44	10	26	30	110	5.73	<1	0.18	<10	1.84	3077	<2	0.01	20	1734	37	1.60	<5	10	187	<5	0.12	<10	<10	148	<10	112	3
84456	0.6	2.28	101	43	0.7	<5	11.04	4	24	32	96	4.79	<1	0.16	<10	1.86	3389	<2	0.01	22	1441	30	0.58	<5	9	204	<5	0.10	<10	<10	133	<10	392	3
84457	1.7	1.53	229	52	<0.5	<5	>15.00	7	11	23	14	3.86	<1	0.14	<10	1.11	6036	2	0.01	7	1080	32	1.01	<5	7	344	<5	0.05	<10	<10	93	<10	363	2
84458	0.3	2.46	90	59	<0.5	<5	6.70	4	29	29	73	6.15	<1	0.18	<10	2.08	2808	<2	0.01	12	1686	60	2.07	<5	7	141	<5	0.07	<10	<10	129	<10	445	3
84459	0.5	2.57	541	61	0.6	<5	8.92	9	27	30	85	5.84	<1	0.17	<10	2.17	3062	<2	0.01	12	1552	58	1.15	<5	10	174	<5	0.12	<10	<10	162	<10	220	3
84460	0.8	2.37	718	54	0.6	<5	11.13	32	25	31	67	5.57	<1	0.16	<10	1.84	4313	<2	0.01	11	1398	78	1.14	<5	10	229	<5	0.07	<10	<10	142	28	2377	3
84461	4.0	2.02	>10000	82	<0.5	<5	8.52	226	24	31	107	5.82	<1	0.17	<10	1.50	3808	<2	0.01	10	1422	2413	2.11	35	9	186	<5	0.02	<10	<10	135	58	4964	3
84462	5.1	1.99	5764	62	<0.5	<5	9.02	121	25	44	163	5.67	1	0.14	<10	1.50	3603	<2	0.01	9	1211	2912	2.08	16	8	205	<5	0.07	<10	<10	129	46	4011	3
84463	0.6	1.98	211	61	0.8	<5	8.89	3	29	33	90	5.45	<1	0.25	<10	1.35	2990	<2	0.01	14	1571	39	1.76	<5	8	176	<5	0.13	<10	<10	131	<10	120	3
84464	0.8	2.95	477	52	0.8	<5	7.64	7	27	35	93	6.08	<1	0.20	<10	2.46	3314	<2	0.01	14	1592	56	0.94	<5	10	158	<5	0.13	<10	<10	154	<10	156	3
84465	<0.2	2.94	128	42	1.0	<5	10.90	3	27	42	58	5.85	<1	0.13	<10	2.70	2846	<2	0.01	12	1463	12	0.63	<5	15	235	<5	0.14	<10	<10	199	<10	206	4
84466	0.3	2.62	163	46	0.8	<5	10.38	2	27	35	51	5.76	<1	0.18	<10	2.37	2753	<2	0.01	13	1500	15	1.00	<5	12	218	<5	0.12	<10	<10	159	<10	77	3
84467	0.6	2.53	256	53	0.7	<5	9.56	6	31	25	59	5.63	<1	0.25	<10	2.12	2801	<2	0.01	12	1606	19	0.79	<5	7	209	<5	0.07	<10	<10	95	<10	345	3
84468	0.4	2.31	291	49	0.6	<5	10.41	4	27	34	55	4.97	<1	0.20	<10	1.87	2300	<2	0.01	12	1513	14	0.57	<5	9	190	<5	0.09	<10	<10	108	<10	77	3
84469	0.4	2.29	137	54	0.5	<5	10.68	3	25	31	77	5.40	<1	0.22	<10	1.69	2582	3	0.01	11	1552	11	1.05	<5	8	182	<5	0.07	<10	<10	107	<10	175	3
84470	<0.2	2.09	109	51	<0.5	<5	10.89	<1	22	28	93	4.85	<1	0.17	<10	1.62	2754	<2	0.01	13	1119	12	0.97	7	9	175	6	0.03	<10	<10	123	<10	67	3
84471	<0.2	2.19	50	40	<0.5	<5	13.26	<1	22	33	86	4.72	<1	0.13	<10	1.69	3178	<2	0.01	12	1052	3	0.70	<5	12	184	5	0.06	<10	<10	137	<10	84	3
84472	<0.2	2.22	103	43	<0.5	<5	11.34	<1	24	33	77	5.05	<1	0.14	<10	1.67	2956	<2	0.01	12	1146	6	0.84	<5	10	174	5	0.04	<10	<10	144	<10	59	3
84473	0.4	2.37	143	49	0.5	<5	9.36	1	27	35	75	5.82	<1	0.14	<10	1.92	3016	<2	0.01	13	1247	25	1.61	5	10	147	5	0.08	<10	<10	159	<10	133	4
84474	<0.2	2.04	89	30	<0.5	<5	14.53	<1	18	27	83	4.18	<1	0.07	<10	1.72	4342	<2	0.01	12	873	12	0.48	<5	10	218	5	0.04	<10	<10	138	<10	106	3
84475	2.9	1.40	619	160	0.6	186	7.93	1	47	69	480	5.77	12	0.17	13	0.35	831	125	0.04	71	810	78	2.08	<5	3	106	9	0.11	<10	<10	45	41	79	16
84476	<0.2	3.43	143	31	0.6	<5	7.77	<1	26	40	56	6.18	<1	0.09	<10	3.32	2785	<2	0.01	12	1183	23	0.73	9	14	139	<5	0.09	<10	<10	193	<10	89	4
84477	<0.2	2.08	151	38	0.5	<5	10.65	<1	28	34	71	5.25	<1	0.10	<10	1.85	2659	<2	0.01	14	1299	10	1.73	6	11	159	5	0.08	<10	<10	168	<10	42	4
84478	0.6	2.29	259	132	<0.5	<5	6.43	1	28	46	81	5.67	<1	0.13	<10	2.10	2110	2	0.01	15	1316	63	2.07	8	11	110	<5	0.06	<10	<10	179	<10	123	4
84479	1.3	2.36	839	120	<0.5	<5	8.45	4	26	42	89	5.87	<1	0.11	<10	2.15	2621	<2	0.01	13	1224	191	2.09	18	13	142	<5	0.05	<10	<10	185	<10	458	4
84480	<0.2	2.37	435	51	<0.5	<5	7.97	<1	26	42	75	5.68	<1	0.10	<10	2.22	2299	<2	0.01	12	1267	28	1.91	14	14	138	<5	0.05	<10	<10	203	<10	66	4
84481	<0.2	2.41	83	44	<0.5	<5	9.10	<1	25	37	74	6.15	<1	0.10	<10	2.14	2484	<2	0.01	12	1180	17	2.29	<5	12	148	<5	0.02	<10	<10	175	<10	37	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2690RJ**

Date : Aug-13-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth/Shipment 12

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84482	0.5	2.22	131	39	0.7	<5	8.27	<1	27	33	87	5.79	<1	0.14	<10	1.97	2066	<2	0.01	12	1157	16	2.53	10	10	134	5	0.10	<10	<10	142	<10	34	4
84483	12.7	2.01	1921	52	0.5	<5	11.26	3	23	32	94	5.06	<1	0.16	<10	1.66	2857	<2	0.01	11	1084	207	1.68	28	10	168	5	0.07	<10	<10	133	<10	321	4
84484	0.7	2.05	801	41	0.5	<5	8.15	<1	25	34	89	5.19	<1	0.15	<10	1.83	1941	<2	0.01	11	1203	25	2.14	11	11	126	5	0.08	<10	<10	145	<10	35	4
84485	0.6	2.27	216	69	0.7	<5	8.61	<1	29	38	82	5.46	<1	0.15	<10	2.04	2019	<2	0.01	13	1217	22	2.08	7	13	137	5	0.13	<10	<10	170	<10	33	5
84486	0.2	2.27	64	39	0.7	<5	7.86	<1	24	38	63	5.40	1	0.08	<10	2.00	2144	<2	0.01	11	1287	9	1.53	5	14	129	<5	0.13	<10	<10	191	<10	41	5
84487	<0.2	2.37	65	30	0.6	<5	8.35	<1	26	32	71	5.75	<1	0.07	<10	2.07	2417	<2	0.01	11	1344	9	1.62	6	15	139	5	0.10	<10	<10	197	<10	60	5
84488	<0.2	2.51	73	26	0.6	<5	9.49	<1	24	36	57	5.75	1	0.04	<10	2.05	2486	<2	0.01	10	1350	4	0.87	<5	19	227	<5	0.12	<10	<10	234	<10	73	5
84489	<0.2	2.13	146	31	0.5	<5	8.53	1	22	37	41	5.07	1	0.09	<10	1.54	2310	<2	0.01	9	1181	19	0.49	<5	16	129	6	0.07	<10	<10	183	<10	173	4
84490	<0.2	1.95	183	36	0.7	<5	8.87	1	25	42	53	5.40	<1	0.11	<10	1.38	2886	<2	0.01	11	1398	21	1.23	5	17	149	<5	0.08	<10	<10	197	<10	130	5
84491	<0.2	2.84	70	36	0.7	<5	6.94	3	28	38	106	6.73	1	0.07	<10	2.20	3147	<2	0.01	12	1467	198	1.18	6	19	149	<5	0.08	<10	<10	244	<10	407	6
84492	<0.2	2.91	81	34	<0.5	<5	7.24	3	25	41	97	6.39	1	0.03	<10	2.36	3128	<2	0.01	11	1450	262	0.53	5	23	153	<5	0.01	<10	<10	287	<10	443	4
84493	0.2	2.31	85	45	<0.5	<5	7.62	1	21	32	52	5.94	<1	0.07	<10	2.03	2772	<2	0.01	10	1340	98	1.34	<5	20	192	5	0.01	<10	<10	208	<10	130	4
84534	<0.2	0.28	157	62	<0.5	<5	>15.00	5	6	12	14	2.57	1	0.09	10	0.35	7095	<2	0.01	4	299	18	0.25	6	6	344	<5	<0.01	<10	<10	34	<10	510	1
84535	0.3	1.48	220	51	<0.5	<5	>15.00	10	19	26	81	4.88	<1	0.14	<10	1.54	4402	<2	0.01	8	718	105	1.05	7	8	223	<5	<0.01	<10	<10	86	<10	943	3
84536	0.2	3.87	249	29	<0.5	<5	10.64	3	49	38	64	8.48	<1	0.10	<10	3.74	4547	<2	0.01	13	989	27	3.07	5	14	172	<5	0.04	<10	<10	182	<10	202	5
84537	0.8	1.93	196	65	0.5	<5	7.12	9	31	37	87	6.68	1	0.28	<10	1.43	2768	<2	0.01	15	1285	40	4.36	9	8	112	<5	0.08	<10	<10	127	<10	824	5
84538	3.3	2.44	126	51	<0.5	<5	7.82	64	28	34	534	6.02	<1	0.15	<10	2.04	3101	<2	0.01	12	1191	720	2.20	7	9	120	5	0.05	<10	<10	149	<10	6209	4
84539	<0.2	2.67	93	55	0.5	<5	9.90	2	30	41	57	5.34	<1	0.21	<10	2.25	2453	<2	0.01	13	1205	8	0.97	5	11	161	<5	0.08	<10	<10	167	<10	72	4
84540	<0.2	2.78	61	48	0.6	<5	10.22	2	26	43	51	5.73	<1	0.12	<10	2.40	2682	<2	0.01	13	1172	10	0.81	<5	15	207	<5	0.09	<10	<10	201	<10	100	5
84541	0.6	3.00	83	73	<0.5	<5	7.42	2	27	46	100	6.70	1	0.12	<10	2.56	2847	<2	0.01	15	1244	93	1.16	<5	14	156	<5	0.01	<10	<10	205	<10	150	4
84542	<0.2	2.35	93	63	<0.5	<5	9.97	2	27	42	67	5.88	<1	0.16	<10	2.42	3572	<2	0.01	14	1171	26	0.79	5	17	215	5	0.03	<10	<10	183	<10	111	4
84543	<0.2	2.97	82	56	0.6	<5	9.76	18	32	44	79	6.14	<1	0.13	<10	2.61	3176	<2	0.01	15	1273	12	0.91	6	16	203	<5	0.07	<10	<10	214	<10	1697	5
84544	<0.2	2.91	109	47	0.7	<5	11.55	2	30	40	28	5.97	1	0.15	<10	2.41	3192	<2	0.01	14	1262	4	0.63	<5	15	221	<5	0.10	<10	<10	208	<10	70	5
84545	<0.2	2.81	79	57	0.7	<5	9.50	8	29	40	83	6.32	1	0.17	<10	2.24	3275	<2	0.01	14	1303	31	1.31	5	13	176	<5	0.12	<10	<10	188	<10	713	5
84546	<0.2	2.95	66	46	0.7	<5	8.84	4	26	42	88	6.14	<1	0.12	<10	2.42	3094	<2	0.01	14	1291	71	0.86	<5	14	170	<5	0.12	<10	<10	199	<10	240	5
84547	<0.2	2.94	76	51	0.8	<5	9.61	2	27	45	45	6.16	<1	0.13	<10	2.42	2686	<2	0.01	15	1338	2	0.78	<5	18	192	<5	0.13	<10	<10	229	<10	72	5
84548	<0.2	3.02	74	68	0.7	<5	13.20	4	26	46	35	6.16	1	0.14	<10	2.49	3576	<2	0.01	15	1309	15	0.68	<5	16	266	<5	0.06	<10	<10	209	<10	291	5
84549	<0.2	2.89	77	91	0.7	<5	10.62	2	25	49	37	5.81	1	0.13	<10	2.53	3448	<2	0.01	13	1209	38	0.74	<5	14	214	<5	0.07	<10	<10	187	<10	127	4
84550	<0.2	1.17	<5	246	0.7	<5	0.82	1	8	105	<1	2.18	1	0.54	<10	0.67	639	<2	0.10	6	713	6	0.01	<5	3	78	7	0.14	<10	<10	47	<10	53	3
84551	1.5	3.23	255	54	0.6	<5	5.39	16	31	45	219	7.28	1	0.17	<10	2.76	3162	<2	0.01	15	1201	916	2.11	21	12	108	<5	0.10	<10	<10	177	<10	1617	5

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2690RJ**

Date : Aug-13-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth/Shipment 12

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84552	0.5	3.34	148	51	0.7	<5	6.54	2	34	49	117	7.33	1	0.17	<10	3.00	3346	<2	0.01	17	1391	74	2.16	9	12	110	<5	0.13	<10	<10	184	<10	102	5
84553	<0.2	2.63	95	47	0.6	<5	9.79	2	26	39	74	5.21	1	0.18	<10	2.18	3343	<2	0.01	13	1171	69	0.87	5	11	135	<5	0.10	<10	<10	155	<10	96	4
84554	<0.2	2.74	72	47	0.6	<5	10.19	3	32	43	58	5.49	1	0.22	<10	2.19	3228	<2	0.01	16	1402	40	0.94	6	11	146	<5	0.12	<10	<10	141	<10	217	4
84555	<0.2	3.08	211	63	0.9	<5	13.30	2	42	42	30	5.83	<1	0.29	<10	2.33	4118	<2	0.01	17	1562	25	0.57	9	13	210	5	0.14	<10	<10	146	<10	68	6
84556	0.5	2.90	41	55	0.8	<5	6.26	2	32	51	89	6.71	<1	0.07	<10	2.60	2745	<2	0.01	15	1368	56	1.90	6	21	119	<5	0.14	<10	<10	259	<10	64	7
84557	1.0	2.72	87	52	0.6	<5	7.44	2	26	45	117	5.41	<1	0.07	<10	2.46	2665	<2	0.01	13	1273	76	0.91	7	16	131	<5	0.10	<10	<10	210	<10	107	5
84558	0.5	2.73	138	54	0.7	<5	10.38	3	27	39	95	5.53	<1	0.07	<10	2.35	3061	<2	0.01	12	1181	64	0.57	7	14	185	<5	0.08	<10	<10	185	<10	201	6
84559	<0.2	3.60	44	40	0.7	<5	8.49	3	32	45	88	6.67	<1	0.03	<10	3.46	3525	<2	0.01	14	1341	12	0.76	6	24	211	<5	0.11	<10	<10	258	<10	211	7
84560	0.7	3.10	31	43	0.7	<5	4.57	6	30	50	90	6.57	<1	0.04	<10	3.02	2803	<2	0.02	15	1309	27	1.64	8	25	83	<5	0.13	<10	<10	257	<10	650	7
84561	1.0	2.79	53	66	0.8	<5	6.20	3	32	47	76	6.30	<1	0.13	<10	2.50	2909	<2	0.01	15	1294	14	1.92	6	15	129	<5	0.16	<10	<10	203	<10	160	6
84562	2.2	1.48	281	67	0.6	<5	5.37	3	34	29	89	7.16	<1	0.28	<10	1.06	2374	<2	0.01	17	1430	145	>5.00	11	7	113	<5	0.13	<10	<10	106	<10	148	5
84563	2.4	1.12	798	55	<0.5	<5	13.15	21	21	23	82	7.38	<1	0.22	<10	0.70	3846	<2	0.01	11	924	463	>5.00	14	5	232	<5	0.08	<10	<10	62	<10	2290	5
84564	<0.2	2.75	99	44	0.5	<5	12.61	3	24	34	131	7.82	<1	0.21	<10	1.91	4532	<2	0.01	11	1156	33	2.65	<5	9	200	<5	0.09	<10	<10	129	<10	125	5
84565	<0.2	2.39	101	59	0.8	<5	11.77	1	28	32	40	5.59	<1	0.21	<10	1.82	3865	<2	0.01	12	1236	16	1.24	<5	10	286	<5	0.13	<10	<10	126	<10	55	5
84566	<0.2	2.31	224	53	0.8	<5	10.97	2	25	35	14	4.53	<1	0.20	<10	1.86	3559	<2	0.01	12	1161	63	0.46	<5	10	201	<5	0.11	<10	<10	120	<10	141	4
84567	0.7	2.15	128	54	0.6	<5	9.82	8	24	43	109	5.26	<1	0.21	<10	1.67	3338	<2	0.01	14	1097	301	1.72	<5	8	183	<5	0.08	<10	<10	93	<10	764	4
84568	0.5	2.26	153	63	0.5	<5	10.79	6	27	32	65	6.23	<1	0.27	<10	1.59	3975	<2	0.01	13	1052	321	2.74	6	7	227	<5	0.10	<10	<10	99	<10	512	4
84569	0.3	3.13	99	130	0.7	<5	6.22	5	32	37	82	7.26	<1	0.32	<10	2.31	3334	<2	0.01	15	1450	241	2.22	<5	10	134	<5	0.13	<10	<10	155	<10	353	5
84570	0.7	2.65	104	110	0.5	<5	7.48	6	28	33	102	6.30	<1	0.24	<10	2.03	3179	<2	0.01	14	1338	234	1.98	6	8	155	<5	0.09	<10	<10	135	<10	561	4
84571	<0.2	2.19	217	60	0.5	<5	9.58	2	28	31	60	5.08	<1	0.24	<10	1.71	2743	<2	0.01	12	1311	21	1.48	5	9	181	<5	0.08	<10	<10	117	<10	111	3
84572	<0.2	2.31	117	58	<0.5	<5	8.16	4	25	31	78	5.36	<1	0.23	<10	1.83	2551	<2	0.01	12	1213	15	1.54	6	9	167	<5	0.06	<10	<10	124	<10	283	3
84573	0.2	2.56	98	81	0.6	<5	7.72	3	29	40	80	5.74	<1	0.19	<10	2.23	2690	<2	0.01	16	1291	12	1.68	6	9	174	<5	0.09	<10	<10	130	<10	170	4
84574	<0.2	3.13	76	120	0.6	<5	7.39	4	28	55	81	6.29	<1	0.23	<10	2.74	2962	<2	0.01	17	1339	6	1.27	<5	10	167	<5	0.08	<10	<10	151	<10	322	4
84575	<0.2	2.07	321	57	<0.5	<5	10.62	1	25	35	56	4.69	<1	0.20	<10	1.70	3423	<2	0.01	13	1141	8	1.31	6	8	239	<5	0.05	<10	<10	125	<10	59	3
84575 A	<0.2	1.11	<5	240	0.7	<5	0.72	<1	8	90	<1	2.14	<1	0.54	<10	0.67	630	<2	0.08	6	705	3	0.02	<5	3	66	6	0.13	<10	<10	45	<10	50	3
84576	0.8	1.46	177	59	<0.5	<5	6.90	7	29	25	98	6.11	<1	0.23	<10	1.19	2908	<2	0.01	15	1285	32	4.06	8	6	177	<5	0.06	<10	<10	102	<10	598	4
84577	0.7	1.40	125	72	<0.5	<5	6.83	6	29	30	89	6.06	<1	0.28	<10	1.11	2953	<2	0.01	15	1354	40	4.68	8	6	175	<5	0.07	<10	<10	91	<10	547	4
84578	1.3	1.44	151	71	0.5	<5	6.20	9	36	29	123	6.95	<1	0.25	<10	1.20	3174	<2	0.01	16	1338	36	>5.00	6	6	153	<5	0.12	<10	<10	111	<10	788	4
84579	0.9	1.51	173	83	0.5	<5	8.24	13	30	35	74	6.79	<1	0.29	<10	1.26	3809	<2	0.01	15	1279	42	>5.00	9	7	199	<5	0.10	<10	<10	114	<10	1401	5
84580	3.3	0.90	146	86	0.5	<5	8.67	8	31	27	60	6.28	<1	0.32	<10	0.64	2908	<2	0.01	16	1358	604	>5.00	14	6	180	<5	0.09	<10	<10	76	<10	782	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2690RJ**

Date : Aug-13-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth/Shipment 12

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84581	0.5	0.43	104	73	0.5	<5	9.55	1	25	21	68	3.63	<1	0.33	<10	0.17	2507	<2	0.01	12	1123	47	3.24	14	5	212	<5	0.06	<10	<10	25	<10	52	2
84582	1.6	0.96	234	59	0.5	<5	5.23	2	24	27	65	5.47	<1	0.27	<10	0.82	2349	<2	0.01	13	1038	62	4.67	15	5	134	<5	0.08	<10	<10	43	<10	71	3
84583	35.1	1.97	402	33	<0.5	<5	10.78	46	18	39	417	6.73	<1	0.12	<10	2.29	5243	<2	0.01	10	706	2859	4.83	39	7	295	<5	0.06	<10	<10	80	<10	4366	4
84584	4.5	1.47	320	54	0.5	<5	5.19	4	27	28	82	7.96	<1	0.29	<10	1.50	2645	<2	0.01	13	1184	313	>5.00	21	5	151	<5	0.10	<10	<10	59	<10	265	5
84585	1.4	0.99	170	69	0.5	<5	7.59	2	27	30	73	5.98	<1	0.30	<10	0.85	2761	<2	0.01	14	1182	96	>5.00	12	5	184	<5	0.09	<10	<10	46	<10	93	4
84586	1.4	2.18	151	60	<0.5	<5	8.90	4	25	38	59	6.23	<1	0.26	<10	2.36	3703	<2	0.01	12	1146	157	4.62	7	6	240	<5	0.06	<10	<10	95	<10	310	4
84587	1.2	1.53	124	74	0.5	<5	5.90	2	31	43	74	5.97	<1	0.36	<10	1.42	2519	<2	0.01	16	1390	93	4.97	10	6	165	<5	0.10	<10	<10	73	<10	131	4
84588	1.9	1.54	104	59	0.5	<5	5.00	4	28	32	93	6.75	<1	0.31	<10	1.47	2462	<2	0.01	14	1196	201	>5.00	15	5	148	<5	0.10	<10	<10	85	<10	290	4
84589	2.7	1.25	189	64	<0.5	<5	5.67	8	24	40	81	6.01	<1	0.28	<10	1.17	2638	<2	0.01	12	1123	406	4.67	13	5	142	<5	0.08	<10	<10	61	<10	901	4
84590	2.1	1.28	182	59	<0.5	<5	4.86	4	27	24	73	6.62	<1	0.33	<10	1.12	2304	<2	0.01	13	1319	230	>5.00	13	4	121	<5	0.07	<10	<10	54	<10	281	4
84591	2.1	1.48	493	65	0.5	<5	6.28	6	29	35	79	7.02	<1	0.31	<10	1.38	2984	<2	0.01	14	1273	215	>5.00	12	5	154	<5	0.09	<10	<10	71	<10	542	4
84592	1.5	1.96	129	89	<0.5	<5	9.02	2	22	53	59	5.67	<1	0.27	<10	2.08	4428	<2	0.01	11	1036	87	3.92	11	6	236	<5	0.06	<10	<10	73	<10	144	4
84593	1.0	1.34	204	76	<0.5	<5	10.64	2	23	50	68	5.82	<1	0.28	<10	1.28	3678	<2	0.01	12	1010	57	4.66	15	6	203	<5	0.07	<10	<10	55	<10	138	4
84594	0.5	1.66	131	63	0.5	<5	7.16	3	26	34	63	6.33	<1	0.23	<10	1.74	2836	<2	0.01	13	1187	49	4.74	7	5	186	<5	0.08	<10	<10	64	<10	216	4
84595	0.9	1.32	86	63	0.5	<5	6.66	2	28	36	87	6.20	<1	0.28	<10	1.27	2587	<2	0.01	14	1202	73	>5.00	6	5	220	<5	0.09	<10	<10	59	<10	117	4
84596	1.4	1.83	188	75	<0.5	<5	7.08	3	30	34	69	7.55	<1	0.31	<10	1.68	2557	<2	0.01	15	1252	195	>5.00	7	6	174	<5	0.07	<10	<10	88	<10	167	5
84597	0.7	1.99	134	85	0.5	<5	4.86	3	32	38	100	6.37	<1	0.34	<10	1.67	2066	<2	0.01	16	1351	75	4.11	7	7	134	<5	0.08	<10	<10	91	<10	222	4
84598	0.5	1.52	123	80	<0.5	<5	7.86	2	28	30	87	5.60	<1	0.31	<10	1.14	2496	<2	0.01	14	1171	55	3.86	6	6	168	<5	0.05	<10	<10	73	<10	126	4
84599	0.3	2.32	70	58	<0.5	<5	8.97	3	27	37	88	6.08	<1	0.21	<10	1.90	3121	<2	0.01	13	1164	114	2.62	5	8	180	<5	0.04	<10	<10	126	<10	233	4
84600	155.7	1.32	163	215	0.5	96	5.74	2	16	135	3734	3.94	4	0.36	11	0.23	733	64	0.06	35	684	200	1.28	192	2	180	5	0.08	<10	<10	32	13	228	13
84601	0.8	4.48	112	110	<0.5	<5	9.17	3	43	59	127	9.78	<1	0.42	11	3.56	4120	<2	0.01	20	2076	38	2.76	8	14	188	<5	0.05	<10	<10	227	<10	146	6
84602	1.0	2.98	86	75	<0.5	<5	7.20	2	31	44	101	6.85	1	0.28	<10	2.31	2945	<2	0.01	15	1423	21	2.05	5	9	166	<5	0.03	<10	<10	158	<10	102	4
84603	0.8	2.59	78	79	<0.5	<5	8.70	4	34	35	107	6.61	<1	0.30	<10	1.84	2814	<2	0.01	16	1286	43	2.65	7	9	200	<5	0.02	<10	<10	125	<10	287	4
84604	<0.2	2.61	68	67	<0.5	<5	8.51	2	27	35	71	6.23	<1	0.24	<10	1.91	2917	<2	0.01	13	1283	26	1.81	<5	9	194	<5	0.02	<10	<10	133	<10	142	4
84605	0.2	2.32	119	48	0.5	<5	5.24	2	30	54	81	6.27	<1	0.09	<10	2.09	2309	<2	0.02	15	1351	49	2.51	<5	17	106	<5	0.09	<10	<10	227	<10	90	5
84606	0.4	2.21	54	66	<0.5	<5	6.55	2	27	41	82	5.83	1	0.12	<10	2.42	2037	<2	0.02	13	1332	22	1.94	5	19	172	<5	0.02	<10	<10	206	<10	56	4
84607	<0.2	2.23	42	84	<0.5	<5	6.19	2	26	44	94	6.23	1	0.15	<10	2.28	2009	<2	0.02	13	1383	32	2.24	<5	18	189	<5	0.02	<10	<10	213	<10	66	4
84608	<0.2	3.12	45	63	<0.5	<5	6.40	3	30	54	86	6.54	1	0.07	<10	3.16	2108	<2	0.02	16	1275	47	1.90	6	21	146	<5	0.07	<10	<10	255	<10	171	5
84609	<0.2	2.31	30	123	<0.5	<5	7.21	2	26	53	75	5.85	<1	0.17	<10	2.59	2107	<2	0.02	14	1212	30	1.85	5	17	220	<5	0.01	<10	<10	198	<10	123	4
84610	<0.2	2.67	57	99	<0.5	<5	5.60	2	26	50	84	6.42	1	0.07	<10	2.67	1966	<2	0.02	15	1231	58	2.19	<5	19	130	<5	0.02	<10	<10	252	<10	109	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2690RJ**

Date : Aug-13-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth/Shipment 12

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84611	0.2	1.54	648	81	<0.5	<5	7.97	3	14	48	20	6.40	<1	0.25	<10	2.09	3421	<2	0.01	9	797	155	1.61	12	11	444	<5	<0.01	<10	<10	85	<10	154	4
84612	1.0	2.36	1681	66	<0.5	<5	10.72	7	23	34	154	5.44	1	0.12	<10	1.88	3627	<2	0.01	11	1076	214	1.26	17	14	253	<5	0.07	<10	<10	171	<10	669	4
84613	0.2	2.68	780	60	0.7	<5	8.27	2	27	48	73	5.73	1	0.14	<10	2.49	2656	<2	0.01	13	1181	82	1.62	10	16	170	<5	0.12	<10	<10	197	<10	129	4
84614	<0.2	2.64	115	126	0.6	<5	8.58	3	27	58	61	5.61	1	0.13	<10	2.36	2376	<2	0.01	14	1186	112	1.26	5	15	166	<5	0.11	<10	<10	189	<10	191	4
84615	0.6	2.42	46	126	0.6	<5	7.36	5	26	91	73	5.29	1	0.15	<10	2.06	2086	<2	0.01	17	1168	442	1.33	<5	13	143	<5	0.11	<10	<10	166	<10	413	4
84616	<0.2	2.80	106	66	0.7	<5	7.54	2	29	40	73	6.23	1	0.22	<10	2.12	2420	<2	0.01	14	1319	60	1.41	<5	13	135	<5	0.13	<10	<10	176	<10	114	5
84617	0.5	2.06	94	63	0.5	<5	6.10	3	26	45	77	5.64	1	0.25	<10	1.36	2023	<2	0.01	13	1014	59	2.01	5	9	95	<5	0.09	<10	<10	123	<10	156	4
84618	0.4	2.69	325	59	0.6	<5	7.61	4	30	38	91	6.02	1	0.20	<10	2.04	2850	<2	0.01	15	1247	132	1.35	8	12	128	<5	0.11	<10	<10	176	<10	298	4
84619	0.4	2.83	201	62	0.7	<5	7.16	4	29	46	84	5.87	1	0.19	<10	2.23	2806	<2	0.01	14	1224	188	0.89	5	13	114	<5	0.12	<10	<10	179	<10	354	5
84620	0.3	2.74	192	73	0.6	<5	5.90	4	30	46	84	5.98	1	0.13	<10	2.49	2321	<2	0.01	14	1286	97	1.61	5	15	97	<5	0.11	<10	<10	214	<10	371	4
84621	<0.2	2.70	45	73	0.7	<5	8.19	2	30	48	73	6.13	1	0.12	<10	2.49	2099	<2	0.01	14	1215	16	1.70	<5	18	135	<5	0.11	<10	<10	228	<10	134	5
84622	0.2	2.39	41	50	0.8	<5	9.55	8	24	42	56	5.37	1	0.10	<10	2.09	2086	<2	0.01	13	1159	534	0.98	<5	17	154	<5	0.12	<10	<10	205	<10	663	6
84623	<0.2	2.47	42	30	0.7	<5	6.86	5	29	52	90	6.07	1	0.07	<10	2.14	2239	<2	0.02	14	1295	23	1.79	<5	19	105	<5	0.12	<10	<10	246	<10	410	6
84624	0.2	2.69	48	40	0.6	<5	4.30	6	31	47	93	6.44	<1	0.07	<10	2.34	2122	<2	0.02	15	1327	51	1.75	<5	14	68	<5	0.11	<10	<10	237	<10	535	5
84625	<0.2	1.03	<5	238	0.6	<5	0.70	1	8	128	<1	2.20	<1	0.50	<10	0.69	619	<2	0.07	7	708	7	0.04	<5	3	57	5	0.12	<10	<10	48	<10	67	3
84626	<0.2	2.96	90	42	0.6	<5	8.30	9	29	43	88	6.74	1	0.14	<10	2.36	3116	<2	0.01	14	1256	66	1.66	<5	14	164	<5	0.10	<10	<10	207	<10	832	5
84627	0.3	2.23	241	56	0.7	<5	7.51	9	27	50	78	5.69	1	0.22	<10	1.53	3091	<2	0.01	14	1242	99	1.79	9	13	106	<5	0.09	<10	<10	172	<10	823	4
84628	<0.2	2.50	104	53	0.7	<5	10.43	6	25	39	75	5.65	1	0.13	<10	2.00	3361	<2	0.01	13	1187	146	1.12	5	15	136	<5	0.11	<10	<10	206	<10	373	5
84629	0.7	3.09	77	54	1.2	<5	9.28	2	29	45	68	5.22	<1	0.17	<10	2.49	3105	<2	0.01	12	1629	48	0.60	<5	15	211	<5	0.16	<10	<10	200	<10	178	6
84630	2.7	2.33	1458	123	0.7	<5	7.28	26	25	42	109	5.52	<1	0.17	<10	1.76	3084	<2	0.01	10	1380	79	1.90	<5	13	121	<5	0.09	<10	<10	168	<10	351	4
84631	1.8	3.13	413	141	0.7	<5	6.07	14	30	62	139	6.07	<1	0.14	<10	2.63	3453	<2	0.01	13	1598	668	1.55	<5	16	119	<5	0.10	<10	<10	214	11	794	4
84632	1.3	2.34	82	228	1.1	<5	9.96	3	28	49	100	5.51	<1	0.07	<10	1.89	2647	<2	0.01	11	1573	272	1.90	<5	12	234	<5	0.18	<10	<10	187	<10	156	8
84633	0.2	2.94	60	64	1.3	<5	6.53	<1	32	52	66	4.94	<1	0.05	<10	2.98	2650	<2	0.02	12	1617	30	0.72	<5	9	192	<5	0.21	<10	<10	197	<10	96	8
84634	0.3	2.76	101	72	1.2	<5	9.58	1	30	46	37	5.14	<1	0.05	<10	2.39	2739	<2	0.01	12	1549	30	0.84	<5	14	267	<5	0.17	<10	<10	199	<10	97	8
84635	0.4	2.79	63	64	1.0	<5	8.32	2	27	52	61	5.43	<1	0.06	<10	2.59	2950	<2	0.01	12	1590	104	1.43	<5	19	243	<5	0.17	<10	<10	228	<10	245	8
84636	7.0	3.26	1752	83	<0.5	<5	6.68	66	25	39	140	6.43	<1	0.15	<10	2.85	2851	<2	0.01	10	1657	2006	1.36	8	16	492	<5	0.01	<10	<10	208	39	3584	4
84637	0.4	2.72	101	68	0.8	<5	7.23	2	21	45	57	4.80	<1	0.14	<10	2.28	2762	<2	0.01	12	1552	59	0.55	<5	16	209	<5	0.11	<10	<10	198	<10	168	4
84638	1.3	3.23	141	68	0.7	<5	6.60	4	29	43	140	6.41	<1	0.10	<10	2.74	2668	<2	0.01	12	1595	587	1.44	<5	18	140	<5	0.11	<10	<10	234	<10	323	5
84639	<0.2	2.38	38	85	0.9	<5	9.22	<1	22	43	38	5.00	<1	0.11	<10	2.00	2045	<2	0.01	10	1454	19	0.29	<5	18	159	<5	0.13	<10	<10	207	<10	85	6
84640	1.2	2.69	107	68	0.8	<5	7.00	15	25	37	118	5.52	<1	0.21	<10	1.88	2663	<2	0.01	11	1588	393	1.31	<5	14	114	<5	0.11	<10	<10	181	16	1318	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2690RJ**

Date : Aug-13-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth/Shipment 12

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84641	0.8	2.03	51	53	0.9	<5	9.24	<1	19	37	93	4.49	<1	0.12	<10	1.46	2370	<2	0.01	9	1461	12	0.56	<5	14	160	<5	0.13	<10	<10	188	<10	84	5
84642	0.7	2.37	71	48	0.8	<5	9.69	<1	28	43	74	4.92	<1	0.07	<10	1.80	2124	<2	0.01	10	1489	17	0.70	<5	12	177	<5	0.12	<10	<10	197	<10	70	6
84643	2.2	2.34	81	51	0.9	<5	8.88	2	27	45	313	4.59	<1	0.08	<10	1.81	2272	<2	0.01	11	1559	46	0.95	<5	10	235	<5	0.13	<10	<10	166	<10	270	6
84644	0.8	2.68	117	74	0.9	<5	8.87	3	28	39	67	4.90	<1	0.07	<10	2.43	2732	<2	0.01	11	1526	69	0.56	<5	11	225	<5	0.14	<10	<10	195	<10	272	6
84645	0.6	2.64	41	162	0.8	<5	5.46	1	27	50	88	5.71	<1	0.05	<10	2.45	2323	<2	0.03	12	1709	86	1.81	<5	11	118	<5	0.14	<10	<10	224	<10	214	7
84646	<0.2	2.97	30	78	0.7	<5	6.18	<1	19	39	64	5.26	<1	0.05	<10	3.04	2114	<2	0.02	11	1694	22	0.73	<5	15	146	<5	0.10	<10	<10	230	<10	71	6
84647	0.2	2.73	68	62	<0.5	<5	7.60	<1	26	43	58	5.12	<1	0.09	<10	2.47	2337	<2	0.02	11	1524	28	0.93	<5	15	220	<5	0.02	<10	<10	209	<10	91	3
84648	0.5	3.53	96	65	<0.5	<5	4.89	3	27	42	93	6.18	<1	0.09	<10	3.20	2409	<2	0.02	11	1661	43	0.88	<5	16	86	<5	0.04	<10	<10	244	<10	310	4
84649	1.9	2.90	70	258	<0.5	<5	5.03	5	24	53	109	5.79	<1	0.18	<10	2.50	2118	<2	0.03	15	1606	162	1.57	<5	15	105	<5	0.03	<10	<10	219	<10	532	4
84650	174.3	0.98	224	229	0.6	79	5.42	5	17	23	3589	3.57	4	0.18	<10	0.20	711	77	0.03	33	744	228	1.40	236	2	200	<5	0.09	<10	<10	25	18	242	12
84651	0.9	3.01	114	64	<0.5	<5	5.52	8	26	39	92	5.98	<1	0.16	<10	2.61	2438	<2	0.01	12	1630	86	1.73	<5	13	118	<5	0.01	<10	<10	205	11	849	3
84652	3.6	1.84	1434	118	<0.5	<5	7.98	47	21	28	111	5.24	<1	0.25	<10	1.75	3632	<2	0.01	9	1430	1019	1.99	5	10	280	<5	<0.01	<10	<10	103	27	2421	3
84653	4.0	2.19	1866	119	<0.5	<5	9.24	14	26	45	201	5.78	<1	0.19	<10	1.79	3399	<2	0.01	14	1208	712	1.40	19	13	214	<5	<0.01	<10	<10	165	<10	1411	3
84654	1.7	2.29	210	141	<0.5	<5	6.84	3	28	71	94	6.58	<1	0.19	<10	1.89	2466	<2	0.02	15	1326	93	2.84	8	14	120	<5	0.02	<10	<10	201	<10	120	4
84655	0.4	2.29	194	71	0.6	<5	6.12	2	30	59	100	6.07	<1	0.19	<10	1.89	1765	<2	0.02	16	1423	33	2.27	9	17	105	<5	0.07	<10	<10	231	<10	63	5
84655 A	<0.2	2.32	214	51	0.6	<5	7.21	2	28	68	83	6.30	<1	0.09	<10	2.11	1924	<2	0.01	15	1219	22	2.47	9	18	104	<5	0.07	<10	<10	228	<10	54	5
84656	<0.2	2.53	43	52	0.6	<5	7.59	2	30	52	61	5.95	<1	0.09	<10	2.38	1993	<2	0.02	15	1250	12	1.85	<5	18	123	<5	0.09	<10	<10	237	<10	57	6
84657	<0.2	2.66	63	46	0.7	<5	7.80	2	30	52	70	6.16	<1	0.09	<10	2.52	2042	<2	0.02	15	1259	33	2.00	<5	18	118	<5	0.11	<10	<10	237	<10	71	6
84658	0.2	2.70	37	43	0.7	<5	4.88	2	36	54	118	6.98	<1	0.05	<10	2.79	1762	<2	0.03	17	1421	29	2.62	5	16	97	<5	0.12	<10	<10	270	<10	71	8
84659	<0.2	2.52	48	65	0.7	<5	5.77	2	32	58	93	6.60	<1	0.06	<10	2.70	1703	<2	0.02	15	1298	15	2.64	5	14	113	<5	0.12	<10	<10	244	<10	47	8
84660	<0.2	2.85	652	52	0.6	<5	8.00	2	31	56	78	6.78	<1	0.05	<10	2.86	2208	<2	0.02	15	1363	16	2.24	12	21	131	<5	0.10	<10	<10	277	<10	57	7
84661	<0.2	2.89	52	50	0.7	<5	4.72	2	31	56	90	6.97	1	0.05	<10	3.05	1960	<2	0.02	15	1324	22	2.46	6	24	96	<5	0.10	<10	<10	282	<10	103	7
84662	0.2	2.11	31	50	0.5	<5	4.12	2	26	39	82	5.71	<1	0.07	<10	2.10	1480	<2	0.02	13	1116	25	2.46	5	19	85	<5	0.08	<10	<10	217	<10	74	6
84663	3.1	1.30	456	130	<0.5	<5	5.99	2	33	67	213	6.32	<1	0.33	<10	1.53	1822	<2	0.02	17	1335	38	3.08	22	13	319	<5	0.01	<10	<10	99	<10	83	4
84664	1.8	0.73	128	136	<0.5	<5	6.67	3	31	37	106	6.22	<1	0.33	<10	1.69	2052	<2	0.02	15	1388	56	2.74	13	14	296	<5	<0.01	<10	<10	69	<10	192	4
84665	0.5	2.21	583	75	<0.5	<5	7.94	6	26	45	107	5.84	<1	0.31	<10	1.58	2070	<2	0.02	16	1349	72	2.11	18	13	151	<5	0.01	<10	<10	145	<10	486	4
84666	0.3	2.23	107	64	<0.5	<5	9.14	2	27	38	90	5.95	<1	0.25	<10	1.75	2042	<2	0.01	14	1221	25	2.43	8	11	179	<5	0.01	<10	<10	138	<10	72	3
84667	0.3	2.20	771	82	<0.5	<5	8.32	5	27	43	98	5.84	<1	0.25	<10	1.74	2577	<2	0.01	14	1261	45	2.32	19	12	181	<5	0.01	<10	<10	155	<10	361	4
84668	0.2	2.29	1809	67	<0.5	<5	7.66	5	28	44	88	5.84	<1	0.16	<10	2.21	2379	<2	0.02	13	1272	29	1.94	39	15	181	<5	0.01	<10	<10	198	<10	405	4
84669	1.7	0.90	187	153	<0.5	<5	8.81	10	24	24	116	5.30	<1	0.48	<10	1.63	2853	<2	0.01	11	1233	429	1.47	11	10	343	<5	<0.01	<10	<10	49	<10	794	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2690RJ**

Date : Aug-13-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth/Shipment 12

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84670	<0.2	0.14	57	44	<0.5	<5	>15.00	5	4	19	12	1.46	1	0.08	<10	0.44	7038	<2	0.01	2	297	39	0.13	<5	4	797	5	<0.01	<10	<10	9	<10	398	1
84671	8.0	0.70	273	76	<0.5	<5	>15.00	102	18	22	393	3.60	1	0.21	<10	1.21	4169	<2	0.01	7	794	151	1.18	163	8	433	<5	<0.01	<10	<10	48	<10	8837	2
84672	14.7	0.81	177	94	<0.5	<5	9.78	20	23	23	236	5.52	<1	0.32	<10	2.26	3244	<2	0.01	11	1173	161	1.12	65	12	844	<5	<0.01	<10	<10	60	<10	1653	3
84673	2.3	0.62	221	109	<0.5	<5	9.00	15	26	20	88	5.98	<1	0.38	<10	2.33	3093	<2	0.01	13	1325	225	1.12	34	10	825	<5	<0.01	<10	<10	44	<10	1105	3
84674	<0.2	2.28	134	85	<0.5	<5	10.85	13	24	29	94	5.36	<1	0.23	<10	2.34	3752	<2	0.01	13	1107	13	0.69	6	10	296	<5	0.01	<10	<10	119	<10	1116	3
84675	<0.2	1.08	<5	260	0.6	<5	0.79	1	8	155	<1	2.25	<1	0.55	<10	0.70	644	<2	0.08	8	715	10	0.02	<5	3	71	5	0.13	<10	<10	45	<10	82	3
84676	1.5	3.05	115	97	<0.5	<5	6.70	5	26	65	206	5.70	<1	0.19	<10	2.74	2655	<2	0.01	13	1616	251	1.14	<5	12	214	<5	0.01	<10	<10	160	<10	403	3
84677	3.3	3.20	160	82	<0.5	5	6.99	53	27	42	273	6.15	<1	0.17	<10	2.89	3172	<2	0.01	12	1480	407	1.41	<5	12	194	<5	<0.01	<10	<10	160	59	4434	3
84678	0.7	2.83	116	110	<0.5	<5	8.95	3	25	40	87	5.43	<1	0.19	<10	2.78	2983	<2	0.01	11	1420	35	0.94	<5	11	266	<5	<0.01	<10	<10	138	<10	237	3
84679	1.0	3.19	85	58	<0.5	<5	8.44	5	27	39	87	5.62	<1	0.15	<10	3.20	2724	<2	0.01	12	1550	217	1.26	<5	13	238	<5	0.01	<10	<10	181	<10	451	3
84680	1.1	2.87	117	75	<0.5	<5	7.70	3	30	50	91	6.51	<1	0.21	<10	2.78	2746	<2	0.01	14	1682	211	3.33	<5	12	202	<5	0.01	<10	<10	176	<10	256	3
84681	0.3	2.80	89	53	<0.5	<5	7.33	2	29	45	87	5.98	<1	0.15	<10	2.54	2926	<2	0.01	13	1548	41	2.16	<5	13	228	<5	0.01	<10	<10	193	<10	154	3
84682	0.8	2.51	63	82	<0.5	<5	7.07	2	30	47	170	5.97	<1	0.19	<10	2.10	2918	<2	0.01	13	1685	21	2.39	<5	14	241	<5	0.04	<10	<10	184	<10	160	4
84683	<0.2	3.06	65	65	<0.5	<5	8.73	1	32	52	86	6.66	<1	0.13	<10	2.82	3351	<2	0.02	14	1707	25	2.24	<5	20	251	<5	0.05	<10	<10	254	<10	124	4
84684	<0.2	3.16	44	70	<0.5	<5	4.55	1	34	59	99	7.07	<1	0.07	<10	3.10	2007	<2	0.02	15	1831	22	2.65	<5	22	139	<5	0.06	<10	<10	289	<10	167	4
84685	<0.2	3.72	321	65	<0.5	<5	2.88	5	42	67	129	7.90	<1	0.07	<10	3.48	1747	<2	0.02	18	1915	27	2.47	<5	26	96	<5	0.10	<10	<10	338	<10	147	5
84686	0.4	1.33	22	56	<0.5	<5	9.51	2	18	105	64	3.73	<1	0.06	<10	1.25	2233	<2	0.02	9	1055	12	1.80	<5	14	640	<5	0.06	<10	<10	129	<10	176	3
84687	<0.2	3.12	170	54	<0.5	<5	5.77	3	34	56	108	6.77	<1	0.06	<10	3.06	2344	<2	0.02	15	1836	35	2.19	<5	25	181	<5	0.08	<10	<10	305	<10	184	5
84688	0.2	2.66	141	72	0.5	<5	9.01	2	31	55	85	5.67	<1	0.14	<10	2.42	2512	<2	0.02	14	1652	61	1.83	<5	16	261	<5	0.06	<10	<10	195	<10	100	3
84770	0.4	0.83	47	81	<0.5	<5	2.18	1	10	90	8	3.40	<1	0.23	<10	0.68	1335	2	0.02	3	856	9	0.68	<5	4	96	<5	<0.01	<10	<10	28	<10	43	2
84771	1.2	0.57	85	82	<0.5	<5	3.20	3	8	90	19	3.43	<1	0.23	<10	0.60	1820	4	0.01	2	787	107	1.12	<5	4	182	<5	<0.01	<10	<10	17	<10	251	2
84772	0.4	0.68	51	124	<0.5	<5	3.69	1	8	75	12	3.23	<1	0.36	<10	0.63	1797	2	0.01	3	933	12	0.65	<5	3	213	<5	<0.01	<10	<10	16	<10	54	4
84773	0.4	0.91	67	65	<0.5	<5	0.96	1	12	111	29	3.22	<1	0.23	<10	0.41	909	5	0.01	5	404	10	0.66	<5	2	39	<5	<0.01	<10	<10	33	<10	58	2
84774	0.2	1.31	56	129	<0.5	<5	2.55	1	16	75	39	3.98	<1	0.29	<10	0.66	1373	6	0.02	4	915	9	0.60	<5	5	91	<5	0.01	<10	<10	78	<10	67	2
84775	<0.2	1.08	<5	246	0.8	<5	0.57	<1	8	164	2	2.14	<1	0.56	10	0.61	589	<2	0.10	7	796	5	<0.01	<5	3	57	5	0.15	<10	<10	39	<10	48	3
84776	0.3	1.22	96	87	<0.5	<5	3.63	2	11	100	32	3.80	<1	0.21	<10	0.83	1626	5	0.02	4	976	14	0.67	<5	6	136	<5	0.02	<10	<10	64	<10	75	3
84777	0.5	1.21	45	71	<0.5	<5	2.64	1	10	76	67	3.79	<1	0.21	<10	0.74	1340	16	0.02	2	927	8	0.65	<5	4	108	<5	0.01	<10	<10	47	<10	59	2
84778	0.3	0.77	29	77	<0.5	<5	2.38	1	8	133	26	3.09	<1	0.24	<10	0.59	1173	8	0.02	4	737	18	0.58	<5	4	107	<5	<0.01	<10	<10	26	<10	68	2
84779	0.3	0.75	78	60	<0.5	<5	1.81	1	8	122	15	2.92	<1	0.20	<10	0.47	968	13	0.02	3	669	11	0.74	<5	3	60	<5	<0.01	<10	<10	26	<10	36	2
84780	0.2	1.16	42	99	<0.5	<5	3.37	1	9	135	20	3.60	<1	0.24	<10	0.68	1419	22	0.02	3	933	14	0.56	<5	5	123	<5	<0.01	<10	<10	39	<10	61	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2690RJ**

Date : Aug-13-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth/Shipment 12

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84781	0.6	0.99	54	178	<0.5	<5	2.41	1	9	66	26	2.76	<1	0.19	<10	0.47	970	8	0.01	2	765	34	0.47	<5	3	50	<5	<0.01	<10	<10	35	<10	60	2
84782	0.3	0.97	42	64	<0.5	<5	2.50	1	8	80	24	2.76	<1	0.18	<10	0.50	1008	5	0.01	3	684	8	0.48	<5	3	43	<5	0.01	<10	<10	35	<10	40	2
84783	0.2	1.18	37	81	<0.5	<5	2.58	1	9	55	15	3.00	<1	0.20	<10	0.62	1066	2	0.02	1	852	48	0.36	<5	3	77	<5	0.03	<10	<10	41	<10	52	2
84784	<0.2	1.20	91	62	<0.5	<5	1.72	1	10	66	17	3.25	<1	0.19	<10	0.66	969	3	0.01	2	883	9	0.61	<5	3	58	<5	<0.01	<10	<10	41	<10	56	2
84785	0.2	1.24	37	70	<0.5	<5	1.47	<1	11	51	21	3.27	<1	0.21	<10	0.62	873	4	0.01	1	1046	9	0.35	<5	3	41	<5	0.01	<10	<10	43	<10	58	2
84786	2.3	0.93	184	64	<0.5	<5	2.72	5	8	51	46	4.05	<1	0.19	<10	0.49	1224	5	0.01	2	676	601	2.47	<5	2	59	<5	<0.01	<10	<10	33	<10	313	2
84787	1.5	0.70	49	51	<0.5	<5	11.29	1	7	34	24	2.31	<1	0.12	<10	0.34	3331	3	0.01	1	528	16	0.90	<5	4	208	<5	<0.01	<10	<10	30	<10	58	1
84788	0.3	1.06	37	63	<0.5	<5	3.77	1	10	50	25	3.28	<1	0.21	<10	0.62	1420	3	0.01	1	883	14	0.52	<5	4	141	<5	<0.01	<10	<10	42	<10	73	2
84789	1.2	1.21	188	80	<0.5	<5	4.80	16	11	38	98	4.81	<1	0.18	<10	0.57	1748	3	0.01	1	767	33	2.72	<5	3	108	<5	0.01	<10	<10	49	18	1373	2
84790	0.6	1.22	76	85	<0.5	<5	2.91	1	11	41	32	3.46	<1	0.25	<10	0.57	1434	5	0.01	2	884	60	0.99	<5	3	88	<5	0.02	<10	<10	38	<10	95	3
84791	0.7	1.16	61	75	<0.5	<5	3.68	1	9	32	23	3.12	<1	0.19	<10	0.63	1708	2	0.01	1	869	40	0.77	<5	3	106	<5	0.02	<10	<10	38	<10	119	2
84792	0.8	1.08	89	70	<0.5	<5	2.61	1	9	50	15	3.35	<1	0.21	<10	0.61	1291	2	0.01	2	865	33	1.33	<5	3	74	<5	0.01	<10	<10	38	<10	55	2
84793	0.3	1.11	45	66	<0.5	<5	2.40	1	8	39	13	3.19	<1	0.20	<10	0.63	1109	2	0.01	1	909	8	0.85	<5	3	75	<5	0.01	<10	<10	40	<10	63	2
139107	2.9	2.15	2551	50	<0.5	<5	6.20	59	17	75	84	5.70	<1	0.12	<10	1.55	2352	<2	0.01	13	1392	455	1.48	10	12	112	<5	<0.01	<10	<10	160	24	1790	3
139108	<0.2	2.40	72	53	<0.5	<5	3.84	1	23	88	99	5.17	<1	0.13	<10	1.94	1604	<2	0.01	18	1723	47	0.81	<5	12	85	<5	0.01	<10	<10	175	<10	112	3
139109	<0.2	3.11	85	63	<0.5	<5	4.34	3	33	110	117	6.21	<1	0.17	<10	2.65	1885	<2	0.01	21	1740	64	0.78	<5	14	107	<5	0.01	<10	<10	203	<10	445	3
139110	<0.2	2.42	81	54	<0.5	<5	3.15	5	28	97	110	5.44	<1	0.13	<10	2.11	1553	<2	0.01	20	1747	45	1.03	<5	13	75	<5	0.01	<10	<10	195	10	677	3
139111	<0.2	2.25	122	60	<0.5	<5	2.33	4	27	91	117	5.29	<1	0.12	<10	1.87	1397	<2	0.01	18	1638	35	0.94	<5	13	51	<5	0.01	<10	<10	198	<10	367	3
139112	0.2	2.61	501	78	<0.5	<5	0.48	10	22	94	90	5.78	<1	0.14	<10	1.99	1754	<2	0.01	18	1738	160	0.29	<5	12	9	<5	0.01	<10	<10	200	<10	333	3
139113	<0.2	2.17	182	73	<0.5	<5	0.74	5	22	87	86	5.19	<1	0.13	<10	1.59	1489	<2	0.01	15	1656	49	0.38	<5	12	15	<5	0.01	<10	<10	182	<10	294	3
139114	<0.2	2.54	145	74	<0.5	<5	0.37	4	18	98	86	5.50	<1	0.10	<10	2.05	1625	<2	0.01	16	1517	56	0.10	<5	13	7	<5	0.01	<10	<10	196	<10	319	3
139115	8.7	1.22	273	92	<0.5	<5	1.62	10	14	11	266	5.73	<1	0.26	<10	0.52	1809	22	0.01	2	1312	842	1.98	<5	3	32	<5	0.01	<10	<10	49	11	831	3
139116	11.1	1.27	228	77	<0.5	<5	1.17	13	20	9	402	5.74	<1	0.28	<10	0.60	1793	13	0.01	3	1337	1265	3.18	<5	3	22	<5	0.01	<10	<10	48	20	1585	3
139117	13.4	1.06	234	67	<0.5	<5	1.31	19	13	19	295	5.94	<1	0.24	<10	0.50	1434	13	0.01	2	1099	2203	3.80	<5	2	28	<5	<0.01	<10	<10	38	29	2447	3
139118	9.4	1.39	149	129	<0.5	<5	1.95	7	12	24	252	4.61	<1	0.30	<10	0.63	1927	23	0.01	2	1167	1102	1.73	<5	2	38	<5	0.01	<10	<10	47	10	728	2
139119	4.4	1.80	100	135	<0.5	<5	2.09	5	17	14	217	4.83	<1	0.27	<10	0.87	2413	14	0.01	3	1368	232	0.96	<5	3	46	<5	<0.01	<10	<10	67	<10	619	2
139120	5.4	0.86	297	111	<0.5	<5	0.69	7	13	38	80	4.96	<1	0.23	<10	0.42	2658	10	0.01	3	910	303	2.62	<5	2	13	<5	<0.01	<10	10	36	<10	497	2
139121	16.5	1.72	132	73	<0.5	<5	0.50	4	14	19	284	7.07	<1	0.20	<10	0.87	1644	31	0.01	<1	1473	1536	0.48	<5	4	9	<5	0.05	<10	<10	103	10	710	4
139122	40.2	1.66	286	103	0.5	<5	0.39	12	13	27	247	6.67	<1	0.21	<10	0.91	1439	13	0.01	<1	1270	2974	1.53	8	5	7	<5	0.11	<10	<10	95	16	1177	4
139123	51.0	0.27	631	42	<0.5	7	0.02	32	5	76	511	10.57	<1	0.16	<10	0.04	152	41	0.01	<1	620	9333	>5.00	26	1	1	<5	<0.01	<10	<10	14	38	3099	5

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2690RJ**

Date : Aug-13-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth/Shipment 12

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139124	96.9	0.54	717	50	<0.5	7	0.60	70	12	61	838	11.82	3	0.11	<10	0.22	961	34	0.01	<1	822	>10000	4.96	34	2	6	<5	<0.01	<10	<10	42	92	7016	6
139125	45.0	0.60	445	50	<0.5	5	0.11	40	8	100	545	8.48	<1	0.11	<10	0.24	987	75	0.01	<1	603	6946	2.22	6	2	2	<5	<0.01	<10	<10	33	85	6849	4
139126	115.2	0.40	1164	75	<0.5	6	0.03	20	3	62	404	10.17	<1	0.16	<10	0.14	335	8	0.01	<1	711	>10000	0.96	17	1	2	<5	<0.01	<10	<10	25	11	836	5
139127	2.6	0.13	97	121	<0.5	<5	0.05	2	3	200	18	1.08	<1	0.09	<10	0.01	2215	6	0.01	4	155	144	0.07	<5	<1	2	<5	<0.01	<10	<10	3	<10	119	<1
139128	4.8	0.15	137	470	<0.5	<5	0.06	3	4	155	40	1.27	<1	0.12	<10	0.02	1430	2	0.01	4	223	151	0.14	<5	1	4	<5	<0.01	<10	<10	3	<10	94	1
139129	5.5	0.17	187	104	<0.5	<5	0.07	4	7	206	57	1.56	<1	0.13	<10	0.02	1473	5	0.01	4	252	150	0.11	7	1	4	<5	<0.01	<10	<10	4	<10	143	1
139130	4.4	0.23	255	173	<0.5	<5	0.07	4	5	148	35	2.97	<1	0.20	<10	0.03	813	2	0.01	4	687	79	0.17	6	2	5	<5	<0.01	<10	<10	6	<10	89	1
139131	4.2	0.25	198	312	<0.5	<5	0.65	3	11	132	37	2.74	<1	0.21	<10	0.09	1835	5	0.01	3	653	67	0.82	<5	2	21	<5	<0.01	<10	<10	7	<10	75	1
139132	1.9	0.15	91	138	<0.5	<5	0.56	2	4	154	14	1.01	<1	0.12	<10	0.02	2346	<2	0.01	4	184	30	0.19	<5	<1	11	<5	<0.01	<10	<10	3	<10	36	1
139133	7.1	0.16	145	170	<0.5	<5	0.13	2	3	204	30	1.41	<1	0.13	<10	0.02	2132	5	0.01	3	284	33	0.05	6	1	6	<5	<0.01	<10	<10	3	<10	34	1
139134	2.0	0.21	88	87	<0.5	<5	0.16	2	4	195	25	1.02	<1	0.08	<10	0.05	1298	<2	0.01	5	169	45	0.04	<5	<1	10	<5	0.02	<10	<10	4	<10	39	1
139135	3.0	0.24	171	73	<0.5	<5	0.05	3	4	156	22	1.61	<1	0.20	<10	0.02	579	4	0.01	2	539	29	0.06	5	1	2	<5	<0.01	<10	<10	5	<10	21	1
139136	2.1	0.13	90	74	<0.5	<5	0.06	1	3	185	14	1.01	<1	0.11	<10	0.02	671	<2	0.01	4	144	16	0.07	<5	<1	2	<5	<0.01	<10	<10	3	<10	18	1
139137	2.9	0.08	55	16	<0.5	<5	0.04	1	2	201	12	0.92	<1	0.06	<10	0.01	176	4	0.01	3	75	14	0.05	<5	<1	1	<5	<0.01	<10	<10	2	<10	11	1
139138	3.1	0.10	68	31	<0.5	<5	0.06	1	1	191	9	0.95	<1	0.08	<10	0.01	114	<2	0.01	4	95	62	0.03	<5	<1	2	<5	<0.01	<10	<10	1	<10	33	1
139139	3.6	0.10	99	40	<0.5	<5	0.04	2	1	181	15	1.05	<1	0.08	<10	0.01	115	4	0.01	3	157	75	0.07	5	<1	2	<5	<0.01	<10	<10	2	<10	39	1
139140	10.7	0.40	57	110	0.8	<5	8.07	1	26	28	210	6.16	<1	0.25	<10	2.07	2156	<2	0.01	12	1622	272	1.88	6	18	527	<5	<0.01	<10	<10	41	<10	111	3
139141	0.5	0.47	42	142	0.7	5	5.89	<1	28	32	99	6.53	<1	0.30	<10	2.19	1903	<2	0.01	12	2186	19	2.21	<5	18	413	<5	<0.01	<10	<10	44	<10	97	3
139142	0.8	0.52	84	96	0.6	5	6.09	1	29	33	76	5.49	<1	0.32	<10	2.14	1784	<2	0.01	12	1837	25	1.67	<5	13	498	<5	<0.01	<10	<10	41	<10	81	2
139143	1.3	0.53	283	170	0.6	6	7.53	5	31	52	85	6.06	<1	0.34	<10	2.26	2035	<2	0.01	14	1864	74	1.95	<5	16	574	<5	<0.01	<10	<10	55	<10	126	3
139144	0.7	0.50	471	157	0.7	5	6.05	7	36	38	82	6.71	<1	0.31	<10	1.27	2026	<2	0.01	17	1850	30	2.77	<5	16	286	<5	<0.01	<10	<10	51	<10	104	3
139145	0.8	0.53	152	156	0.6	6	6.53	3	34	60	99	6.93	<1	0.30	<10	1.96	1950	<2	0.02	16	1942	155	2.93	<5	20	359	<5	<0.01	<10	<10	59	<10	150	3
139146	0.2	0.51	84	146	0.5	7	7.70	1	35	34	96	7.86	<1	0.28	<10	2.27	1958	<2	0.02	14	2009	27	3.52	<5	21	397	<5	<0.01	<10	<10	64	<10	92	4
139147	0.2	0.77	231	110	0.5	6	7.85	3	29	51	85	7.19	<1	0.27	<10	2.28	2361	<2	0.02	13	1742	23	2.97	<5	17	514	<5	<0.01	<10	<10	72	<10	77	3
139148	4.5	0.29	375	169	<0.5	<5	0.11	6	6	128	58	3.90	<1	0.23	<10	0.04	290	52	0.01	4	681	97	1.60	5	1	5	<5	<0.01	<10	<10	5	<10	116	2
139149	4.0	0.40	396	107	<0.5	<5	0.17	8	9	151	30	5.57	<1	0.18	<10	0.12	286	10	0.05	5	1137	307	3.10	<5	2	8	<5	<0.01	<10	<10	16	<10	452	3
139150	3.5	0.43	262	108	<0.5	<5	0.11	5	10	101	46	5.15	<1	0.23	<10	0.12	237	15	0.03	4	894	267	3.27	<5	2	4	<5	<0.01	<10	<10	15	<10	196	2
139151	9.2	0.43	443	90	<0.5	<5	0.05	11	13	223	46	5.19	<1	0.25	<10	0.14	199	14	0.01	8	615	891	3.81	6	1	4	<5	<0.01	<10	<10	19	<10	754	2
139152	3.9	0.82	260	225	<0.5	<5	0.08	5	8	152	44	4.25	<1	0.23	<10	0.43	585	5	0.01	5	811	315	0.85	<5	2	3	<5	<0.01	<10	<10	39	<10	327	2
139153	2.0	0.73	214	306	<0.5	<5	0.06	3	3	230	42	3.61	<1	0.23	<10	0.34	420	7	0.01	6	800	80	0.19	<5	2	11	<5	<0.01	<10	<10	35	<10	96	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2690RJ**

Date : Aug-13-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth/Shipment 12

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139154	>200.0	0.52	511	169	<0.5	<5	0.16	26	5	138	32	3.12	1	0.17	<10	0.16	514	6	0.02	4	602	1576	1.12	32	1	6	<5	<0.01	<10	<10	11	28	2672	2
139155	42.4	0.36	1432	150	<0.5	<5	0.03	32	5	207	81	3.80	1	0.12	<10	0.14	309	6	0.01	6	510	2844	2.09	29	1	2	<5	<0.01	<10	<10	19	15	1423	2
139156	42.0	0.36	546	232	<0.5	<5	0.03	13	3	191	35	3.20	1	0.17	<10	0.13	301	4	0.02	5	536	2564	1.47	19	1	3	<5	<0.01	<10	<10	17	<10	724	2
139157	2.6	1.77	199	239	<0.5	<5	0.39	3	11	54	25	4.76	<1	0.30	13	0.80	1404	<2	0.02	3	1466	248	0.69	<5	2	12	<5	<0.01	<10	<10	41	<10	112	3
139158	5.7	0.83	375	237	<0.5	<5	0.20	6	6	67	16	3.27	<1	0.31	<10	0.22	402	2	0.01	2	1110	250	1.00	6	1	7	<5	<0.01	<10	<10	19	<10	127	2
139159	128.0	0.44	1000	130	<0.5	<5	0.07	29	4	253	80	4.04	<1	0.23	<10	0.09	168	8	0.01	7	565	3271	3.16	47	1	4	<5	<0.01	<10	<10	9	19	1744	2
139160	>200.0	0.53	677	52	<0.5	5	0.10	128	7	139	372	6.41	4	0.19	<10	0.21	419	<2	0.02	4	794	>10000	>5.00	93	1	10	<5	<0.01	<10	<10	19	206	>10000	3
139161	>200.0	0.37	520	78	<0.5	<5	0.04	25	5	234	90	5.40	1	0.19	<10	0.09	195	5	0.02	6	592	4556	4.21	62	1	4	<5	<0.01	<10	<10	13	30	2692	3
139162	>200.0	0.79	701	104	<0.5	<5	0.19	24	10	129	67	5.63	<1	0.20	<10	0.42	963	4	0.01	4	710	2206	3.71	25	1	10	<5	<0.01	<10	<10	33	22	2096	3
139163	6.9	0.50	278	273	<0.5	<5	0.04	4	6	187	13	4.47	<1	0.34	<10	0.15	269	14	0.02	5	1017	112	1.19	7	2	14	<5	0.01	<10	<10	31	<10	61	2
139164	5.3	0.37	376	152	<0.5	<5	0.11	6	10	114	8	3.60	<1	0.18	<10	0.15	377	4	0.01	4	726	128	2.30	5	1	6	<5	0.01	<10	<10	38	<10	107	2
139165	12.7	0.28	233	189	<0.5	<5	0.06	5	4	216	8	2.77	<1	0.13	<10	0.10	242	3	0.02	6	416	252	1.65	7	1	5	<5	<0.01	<10	<10	14	<10	192	1
139166	6.4	0.23	409	153	<0.5	<5	0.05	<1	5	91	<1	2.71	<1	0.20	<10	0.02	49	2	0.02	4	619	189	1.85	14	<1	11	<5	<0.01	<10	<10	7	<10	205	2
139167	4.3	0.41	309	228	<0.5	<5	0.13	<1	5	118	8	2.35	<1	0.27	<10	0.06	122	3	0.01	4	750	109	1.13	9	1	20	<5	<0.01	<10	<10	8	<10	134	2
139168	3.0	0.82	214	169	<0.5	<5	0.19	<1	8	56	12	2.88	<1	0.25	<10	0.23	578	<2	0.01	2	970	115	0.92	<5	1	13	<5	0.02	<10	<10	15	<10	134	2
139169	132.4	1.17	240	146	<0.5	<5	0.75	<1	13	69	8	4.63	<1	0.26	<10	0.46	989	<2	0.01	3	904	55	1.92	15	2	21	<5	0.04	<10	<10	25	<10	77	3
139170	34.1	2.03	56	99	<0.5	<5	1.66	3	14	19	22	5.53	<1	0.15	<10	1.09	1874	<2	0.02	1	1395	127	0.87	5	3	49	<5	0.02	<10	<10	50	<10	366	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Quality Assaying for over 25 Years

Assay Certificate

8V-2698-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 13**
Attn: **Sue Deane**

Aug-15-08

We hereby certify the following assay of 24 core samples submitted Jul-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
84689	0.01	0.02	1.1	
84690	0.01		0.5	
84691	<0.01		0.7	
84692	0.03		1.7	
84693	0.06		1.5	
84694	0.01		0.6	
84695	0.01		1.0	
84696	0.02		1.0	
84697	0.01		1.1	
84698	0.03	0.03	0.7	
84699	0.03		4.2	
84700	0.48		0.4	
84701	0.05		5.7	
84702	0.03		8.0	1.52
84703	0.01		0.9	
84704	0.01		0.6	
84705	0.01		0.4	
84706	<0.01		0.9	
84707	<0.01		1.0	
84708	0.01	0.02	0.7	
84709	0.02		0.4	
84710	0.01		1.1	
84711	0.01		0.7	
84712	0.02		0.7	
*0218	0.94			
*CCu-1c				3.97
*BLANK	<0.01			<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2698-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 13**
Attn: **Sue Deane**

Aug-15-08

We hereby certify the following assay of 24 core samples submitted Jul-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84713	<0.01	<0.01	0.6
84714	0.01		1.2
84715	0.02		0.8
84716	0.03		1.0
84717	0.02		0.8
84718	0.04		2.7
84719	0.03		1.4
84720	0.02		1.0
84721	0.02		0.9
84722	0.03	0.02	0.5
84723	0.01		0.4
84724	0.02		0.9
84725	0.01		1.6
84726	0.03		0.7
84727	0.03		0.6
84728	0.01		1.1
84729	<0.01		0.2
84730	0.03		0.8
84731	0.02		1.3
84732	0.01	0.03	1.1
84733	0.01		1.0
84734	<0.01		0.5
84735	0.01		1.3
84736	0.02		1.7
*0218	0.88		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2698-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 13**
Attn: **Sue Deane**

Aug-15-08

We hereby certify the following assay of 24 core samples
submitted Jul-28-08

Sample Name	Au g/tonne	Au-Rerun g/tonne	Au-Check g/tonne	Ag g/tonne	Ag-Rerun g/tonne	Ag g/tonne	Ag-Rerun g/tonne
84737	0.04	0.02	0.04	3.3	2.8		
84738	0.03	0.05		3.0	2.6		
84739	0.02	0.03		1.4	1.2		
84740	0.02	0.02		1.4	0.9		
84741	0.04	0.04		1.0	0.8		
84742	0.03	0.03		0.6	0.7		
84743	0.01	0.01		0.3	<0.1		
84744	0.01	<0.01		<0.1	<0.1		
84745	0.03	0.03		0.8	0.5		
84746	0.05	0.03	0.04	1.7	1.3		
84747	2.95	2.57		8.9	7.8		
84748	3.60	3.57		31.3	24.1		
84749	0.05	0.03		1.4	1.0		
84750	0.11	0.18		>200	>200	1650	790.0
84751	0.08	0.08		3.1	2.3		
84752	1.09	1.14		3.5	2.3		
84753	0.19	0.22		3.0	2.1		
84754	0.33	0.34		3.1	2.1		
84755	1.02	1.06		3.4	2.9		
84756	0.30	0.32	0.29	1.6	1.3		
84757	0.10	0.11		1.6	2.3		
84758	1.37	0.58		2.1	1.9		
84759	0.12	0.31		1.7	0.9		
84760	0.09	0.10		1.3	1.1		
*0218	0.87	0.90					
*CCu-1c						130.2	129.8
*BLANK	<0.01	<0.01				<0.1	<0.1

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2698-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 13**
Attn: **Sue Deane**

Aug-15-08

We hereby certify the following assay of 24 core samples submitted Jul-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
84761	0.12	0.11	1.7	
84762	0.03		1.0	
84763	0.05		1.4	
84764	0.03		1.5	
84765	0.01		0.8	
84766	0.02		1.3	
84767	0.07		2.3	
84768	0.03		1.3	
84769	0.01		1.1	
84794	0.03	0.03	1.1	
84795	0.03		0.8	
84796	0.28		9.1	
84797	0.57		10.3	
84798	0.18		2.7	
84799	0.11		4.1	
84800	1.02		>200	220.4
84801	0.06		2.9	
84802	0.11		2.7	
84803	0.24		19.4	
84804	0.23	0.22	11.6	
84805	0.62		6.1	
84806	<0.01		<0.1	
84807	0.04		1.8	
84808	0.05		3.2	
*0218	0.88			
*CCu-1c				129.9
*BLANK	<0.01			<0.1

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2698-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 13**
Attn: **Sue Deane**

Aug-15-08

We hereby certify the following assay of 24 core samples submitted Jul-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %	Zn %
84809	0.11	0.11	1.6		
84810	0.06		1.9		
84811	0.11		4.5		
84812	0.73		39.4	2.90	1.12
84813	0.09		3.8		
84814	0.05		0.7		
84815	0.02		0.9		
84816	0.02		0.8		
84817	<0.01		<0.1		
84818	0.04	0.04	0.3		
84819	0.07		<0.1		
84820	0.03		0.1		
84821	0.13		0.8		
84822	0.19		1.1		
84823	0.19		1.2		
84824	0.24		0.8		
84825	<0.01		<0.1		
84826	0.13		2.0		
84827	0.07		0.7		
84828	0.08	0.11	0.6		
84829	0.11		0.7		
84830	0.18		2.1		
84831	0.09		1.5		
84832	0.21		2.0		
*0218	0.87				
*CCu-1c				0.35	3.99
*BLANK	<0.01			<0.01	<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2698-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 13**
Attn: **Sue Deane**

Aug-15-08

We hereby certify the following assay of 24 core samples submitted Jul-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84833	0.06	0.05	0.2
84834	0.06		0.5
84835	0.07		1.5
84836	0.06		0.8
84837	0.05		0.8
84838	0.38		1.8
84839	0.09		1.0
84840	0.15		10.3
84841	0.10		0.9
84842	0.11	0.10	<0.1
84843	0.27		0.8
84844	0.13		0.9
84845	0.07		0.4
84846	1.23		1.6
84847	0.28		0.8
84848	0.05		<0.1
84849	0.08		0.6
84850	0.01		<0.1
84851	0.10		0.3
84852	0.07	0.05	0.5
84853	0.11		0.6
84854	0.05		0.4
84855	0.06		1.1
84856	0.07		0.7
*0218	0.93		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2698-RA7

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 13**
Attn: **Sue Deane**

Aug-15-08

We hereby certify the following assay of 24 core samples submitted Jul-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
84857	0.11	0.09	1.5	
84858	0.26		4.9	
84859	0.35		9.8	
84860	0.20		10.0	
84861	1.34		27.7	
84862	0.91		29.8	1.59
84863	0.78		9.5	
84864	0.58		5.2	
84865	0.23		5.7	
84893A	0.05	0.04	0.2	
84894	0.02		<0.1	
84895	0.03		0.3	
84896	0.05		0.2	
84897	0.04		0.3	
84898	0.03		0.2	
84899	0.02		<0.1	
84900	<0.01		<0.1	
84901	0.10		1.0	
84902	0.03		<0.1	
84903	0.09	0.07	0.7	
84904	0.17		1.1	
84905	0.12		0.4	
84906	0.23		0.7	
84907	0.20		0.1	
*0218	0.90			
*Ccu-1c				3.93
*BLANK	<0.01			<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2698-RA8

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 13**
Attn: **Sue Deane**

Aug-15-08

We hereby certify the following assay of 24 core samples submitted Jul-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
84907A	0.08	0.08	0.6	
84908	0.05		0.2	
84909	0.10		0.3	
84910	0.03		0.2	
84911	0.07		0.3	
84912	0.03		0.1	
84913	0.11		0.9	
84914	0.06		0.7	
84915	0.06		0.3	
84916	0.02	0.02	0.2	
84917	0.03		0.3	
84918	0.08		0.2	
84919	0.01		<0.1	
84920	0.05		0.4	
84921	0.10		1.0	
84922	0.06		1.0	
84923	0.05		1.4	
84924	0.43		2.0	
84925	0.07		>200	755.9
84926	0.09	0.10	2.9	
84927	0.03		3.8	
84928	0.96		2.5	
84929	0.27		0.8	
84930	0.05		0.9	
*0218	0.93			
*CCu-1c				128.7
*BLANK	<0.01			<0.1

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2698-RA9

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 13**
Attn: **Sue Deane**

Aug-15-08

We hereby certify the following assay of 24 core samples submitted Jul-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84931	0.06	0.05	0.7
84932	0.11		0.8
84933	0.06		1.3
84934	0.08		5.8
84935	0.03		1.0
84936	0.34		4.7
139171	0.06		3.8
139172	0.25		19.7
139173	0.21		9.6
139174	1.29	1.39	36.1
139175	0.07		5.0
139176	0.39		9.1
139177	2.81		127
139178	0.05		0.9
139179	0.05		2.9
139180	0.07		1.5
139181	0.07		2.3
139182	0.04		1.7
139183	0.06		1.3
139184	0.05	0.07	8.1
139185	0.02		0.9
139186	0.34		1.6
139187	0.18		2.3
139188	0.17		4.1
*0218	0.92		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2698-RA10

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 13**
Attn: **Sue Deane**

Aug-15-08

We hereby certify the following assay of 24 core samples submitted Jul-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne	Pb %
139189	0.19	0.16	1.3		
139190	0.31		65.3		2.21
139191	0.87		193		
139192	1.70		141		2.14
139193	1.82		175		3.05
139194	0.57		>200	232.7	9.40
139195	0.64		>200	260.4	11.4
139196	0.91		>200	207.7	6.20
139197	1.29		>200	347.5	3.90
139198	4.46	5.07	>200	319.6	11.5
139199	1.17		>200	237.3	2.60
139200	0.28		53.2		
139201	0.16		17.8		
139202	0.50		90.5		
139203	0.12		3.9		
139204	0.06		3.4		
139205	0.32		5.3		
139206	0.10		1.9		
139207	0.08		1.1		
139208	0.02	0.01	3.7		
139209	0.15		2.9		
139210	0.67		4.8		
139211	0.18		1.9		
139212	0.29		19.7		
*0218	0.91				
*CCu-1c				128.7	0.33
*BLANK	<0.01			<0.1	<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2698-RA11

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 13**
Attn: **Sue Deane**

Aug-15-08

We hereby certify the following assay of 24 core samples
submitted Jul-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %	Zn %
139213	0.07	0.07	1.0		
139214	0.06		<0.1		
139215	0.03		<0.1		
139216	0.09		<0.1		
139217	<0.01		0.2		
WDR08-04	0.75		<0.1		
HL08-23 cuttings	0.20		27.0	1.18	1.17
*0218	0.89				
*CCu-1c				0.35	3.99
*BLANK	<0.01				

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2698RJ**

Date : Aug-15-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 13

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84689	1.1	3.22	125	56	<0.5	<5	3.98	2	35	61	102	7.67	<1	0.09	<10	3.05	1822	<2	0.02	20	1714	14	2.43	<5	18	119	<5	0.06	<10	<10	262	<10	95	6
84690	0.5	2.84	65	47	<0.5	<5	6.86	2	31	59	103	6.34	<1	0.06	<10	2.70	2276	<2	0.02	18	1462	9	1.49	<5	18	273	<5	0.03	<10	<10	239	<10	91	4
84691	0.7	3.20	50	79	<0.5	<5	6.83	2	32	55	91	6.91	<1	0.06	<10	3.19	2218	<2	0.02	17	1472	40	1.79	<5	19	168	<5	0.06	<10	<10	251	<10	86	5
84692	1.7	2.23	84	119	<0.5	<5	6.20	3	33	45	106	6.57	<1	0.30	<10	1.88	2596	<2	0.01	18	1592	132	4.06	7	8	156	<5	0.01	<10	<10	133	<10	185	5
84693	1.5	1.69	287	119	<0.5	<5	9.59	2	25	41	73	5.38	<1	0.31	<10	1.34	3091	<2	0.01	14	1625	130	3.43	8	6	230	6	0.01	<10	<10	87	<10	162	4
84694	0.6	2.31	92	108	<0.5	<5	7.31	3	32	40	86	6.17	<1	0.26	<10	2.11	3461	<2	0.01	16	1503	37	2.12	<5	8	187	<5	0.01	<10	<10	126	<10	211	4
84695	1.0	2.60	85	90	<0.5	<5	7.42	2	30	37	112	6.36	<1	0.21	<10	2.42	3450	<2	0.01	14	1573	45	1.99	<5	8	164	<5	0.02	<10	<10	133	<10	137	5
84696	1.0	2.35	392	91	<0.5	<5	8.70	3	28	35	113	5.75	<1	0.24	10	1.97	3142	<2	0.01	14	1471	34	2.37	5	7	174	<5	0.02	<10	<10	133	<10	266	4
84697	1.1	1.72	181	87	<0.5	<5	9.71	2	26	38	88	4.28	<1	0.23	10	1.40	3302	<2	0.02	14	1304	31	1.83	8	7	194	<5	0.05	<10	<10	118	<10	173	3
84698	0.7	2.28	204	102	<0.5	<5	8.24	2	31	38	87	6.23	<1	0.27	10	1.95	3394	<2	0.02	15	1495	34	3.38	7	8	177	<5	0.04	<10	<10	132	<10	84	5
84699	4.2	1.24	425	110	<0.5	<5	9.31	20	31	28	87	6.38	<1	0.32	<10	0.87	3250	<2	0.01	16	1393	709	>5.00	12	5	177	<5	0.01	<10	<10	73	<10	2081	5
84700	0.4	1.15	7385	23	<0.5	17	6.67	<1	198	15	81	4.13	<1	0.04	17	0.26	797	17	0.10	35	1370	9	1.46	8	1	102	<5	0.06	<10	<10	47	<10	100	12
84701	5.7	1.91	411	89	<0.5	<5	8.20	93	36	50	543	6.48	<1	0.26	<10	1.57	3290	<2	0.01	16	1391	299	4.24	15	6	153	<5	0.01	<10	<10	93	<10	9665	4
84702	8.0	2.09	122	83	<0.5	<5	8.84	161	38	40	1445	5.35	<1	0.22	<10	1.85	3072	<2	0.01	14	1198	29	2.62	17	7	240	<5	<0.01	<10	<10	98	<10	>10000	3
84703	0.9	2.04	85	100	<0.5	<5	8.35	3	28	29	101	6.01	<1	0.31	<10	2.16	2772	<2	0.01	14	1523	12	1.82	8	8	185	6	<0.01	<10	<10	91	<10	363	4
84704	0.6	2.58	70	104	<0.5	<5	9.34	2	27	32	77	6.19	<1	0.36	<10	2.02	2580	<2	0.01	13	1557	8	2.33	5	7	203	11	0.02	<10	<10	116	<10	224	4
84705	0.4	2.23	67	106	<0.5	<5	7.16	1	25	29	76	5.81	<1	0.32	<10	1.74	1677	<2	0.01	12	1421	11	2.18	7	6	142	5	0.01	<10	<10	102	<10	45	4
84706	0.9	2.37	42	95	<0.5	<5	9.16	1	25	29	78	5.56	<1	0.28	<10	1.92	1923	<2	0.01	13	1379	4	1.60	5	6	171	8	0.01	<10	<10	109	<10	53	4
84707	1.0	2.21	68	122	<0.5	<5	5.58	1	27	24	88	6.42	<1	0.34	<10	1.84	1636	<2	0.01	12	1568	5	3.32	<5	6	124	7	0.01	<10	<10	103	<10	54	5
84708	0.7	2.51	43	100	<0.5	<5	6.81	1	27	30	79	6.53	<1	0.23	<10	2.50	1878	<2	0.02	13	1478	<2	1.91	7	9	185	8	0.01	<10	<10	137	<10	70	4
84709	0.4	1.67	58	79	<0.5	<5	13.94	1	21	24	60	4.69	<1	0.20	10	1.47	2744	<2	0.02	9	1182	5	1.34	<5	7	287	11	0.01	<10	<10	93	<10	62	3
84710	1.1	1.91	69	90	<0.5	<5	12.65	1	25	23	69	5.26	<1	0.23	11	1.56	2701	<2	0.01	10	1242	7	2.33	<5	7	253	15	0.01	<10	<10	94	<10	69	4
84711	0.7	2.47	111	117	<0.5	<5	11.20	1	24	30	74	5.55	<1	0.28	11	2.01	2588	<2	0.02	11	1456	4	1.61	<5	8	209	12	0.02	<10	<10	118	<10	81	4
84712	0.7	2.66	75	97	<0.5	<5	10.61	2	26	35	78	5.92	<1	0.20	10	2.18	2235	<2	0.02	13	1454	2	1.26	5	10	195	10	0.02	<10	<10	159	<10	136	4
84713	0.6	1.59	59	267	<0.5	<5	8.84	3	22	29	70	4.91	1	0.26	<10	1.54	1846	<2	0.02	11	1306	92	1.30	<5	7	188	5	<0.01	<10	<10	91	<10	114	4
84714	1.2	2.08	88	193	<0.5	<5	7.22	2	25	30	91	5.61	1	0.26	<10	1.64	1845	<2	0.02	11	1416	92	1.84	<5	10	161	8	0.01	<10	<10	128	<10	138	4
84715	0.8	1.68	43	247	<0.5	<5	9.75	2	22	31	85	4.86	1	0.25	10	1.55	2307	<2	0.02	10	1224	122	1.39	<5	9	206	10	0.01	<10	<10	103	<10	112	4
84716	1.0	1.42	250	175	<0.5	<5	8.33	6	22	24	66	4.75	1	0.36	<10	1.20	2130	<2	0.01	9	1245	254	1.90	9	7	179	7	0.01	<10	<10	74	<10	558	3
84717	0.8	1.76	52	194	<0.5	<5	10.10	2	21	25	67	4.65	2	0.30	<10	1.29	2211	<2	0.01	10	1252	65	1.55	<5	6	177	10	0.01	<10	<10	72	<10	90	3
84718	2.7	1.71	154	82	<0.5	<5	7.45	3	24	23	71	5.31	1	0.50	<10	1.03	1905	<2	0.01	11	1356	159	3.56	9	6	148	8	0.02	<10	<10	77	<10	174	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2698RJ**

Date : Aug-15-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 13

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84719	1.4	2.18	61	126	<0.5	<5	7.29	2	24	32	76	5.56	1	0.33	<10	1.66	1798	<2	0.02	10	1353	124	2.43	<5	8	150	10	0.05	<10	<10	110	<10	130	5
84720	1.0	2.19	32	168	<0.5	<5	9.15	2	24	27	75	5.30	<1	0.20	<10	1.66	1877	<2	0.02	10	1317	65	1.63	<5	9	172	9	0.07	<10	<10	123	<10	89	4
84721	0.9	2.02	35	275	<0.5	<5	11.38	3	21	37	67	4.80	2	0.18	10	1.48	2258	<2	0.02	9	1211	120	1.12	<5	10	204	11	0.03	<10	<10	134	<10	143	4
84722	0.5	2.31	76	153	<0.5	<5	10.63	2	22	34	69	5.33	1	0.21	<10	1.60	2774	<2	0.01	10	1303	68	1.01	<5	9	189	8	0.01	<10	<10	126	<10	130	4
84723	0.4	2.39	274	225	<0.5	<5	8.94	2	22	34	59	4.91	1	0.22	<10	1.84	2233	<2	0.01	9	1326	107	0.69	<5	9	172	10	0.03	<10	<10	129	<10	97	4
84724	0.9	2.11	1064	171	<0.5	<5	6.65	2	22	33	80	5.06	<1	0.21	<10	1.74	1664	<2	0.01	9	1336	86	1.60	<5	8	130	6	0.03	<10	<10	125	<10	73	4
84725	1.6	1.16	<5	567	0.6	<5	0.60	3	8	191	4	2.12	1	0.50	11	0.62	583	2	0.10	7	747	279	0.03	<5	3	80	<5	0.15	<10	<10	43	<10	210	4
84726	0.7	2.11	4677	165	<0.5	<5	8.03	1	23	29	70	5.23	<1	0.22	<10	1.72	1810	<2	0.01	10	1293	81	1.66	5	8	150	11	0.03	<10	<10	116	<10	67	4
84727	0.6	2.51	1059	104	<0.5	<5	10.25	3	20	36	63	5.20	1	0.28	<10	1.83	2280	<2	0.01	9	1305	7	0.75	6	10	176	13	0.01	<10	<10	112	<10	268	4
84728	1.1	2.36	435	135	<0.5	<5	9.86	1	22	27	85	4.76	<1	0.34	<10	1.66	2351	<2	0.01	10	1272	11	0.91	5	9	179	14	0.04	<10	<10	109	<10	37	4
84729	0.2	2.58	162	102	<0.5	<5	9.53	1	25	36	60	5.19	<1	0.24	<10	2.20	2227	<2	0.01	11	1250	7	1.13	<5	11	192	10	0.06	<10	<10	144	<10	50	5
84730	0.8	2.66	177	101	0.5	<5	9.53	1	27	36	91	5.68	1	0.25	<10	2.21	2538	<2	0.01	9	1474	12	1.20	<5	11	174	11	0.09	<10	<10	160	<10	59	5
84731	1.3	2.79	63	115	<0.5	<5	5.78	3	25	34	82	6.08	1	0.23	<10	2.33	2181	<2	0.02	12	1518	64	1.47	8	10	125	8	0.03	<10	<10	171	<10	238	5
84732	1.1	2.58	83	117	<0.5	<5	6.50	4	24	29	79	5.74	1	0.17	<10	2.27	2458	<2	0.02	10	1409	126	1.49	<5	10	147	8	0.03	<10	<10	155	<10	356	5
84733	1.0	3.00	47	231	<0.5	<5	6.33	3	25	42	75	5.97	1	0.09	<10	2.94	2019	<2	0.02	11	1381	103	1.10	<5	14	131	10	0.02	<10	<10	206	<10	242	5
84734	0.5	2.76	41	252	<0.5	<5	7.70	1	24	33	74	5.51	1	0.23	<10	2.50	1883	<2	0.02	10	1364	35	1.33	5	11	171	9	0.01	<10	<10	153	<10	118	4
84735	1.3	2.37	132	149	<0.5	<5	5.87	4	23	29	81	5.28	<1	0.30	<10	2.08	2230	<2	0.01	10	1277	165	1.63	6	8	124	9	0.01	<10	<10	116	<10	355	4
84736	1.7	1.34	116	176	<0.5	<5	6.98	4	21	22	51	5.00	1	0.38	<10	1.33	2456	<2	0.01	9	1189	186	1.89	6	7	142	8	<0.01	<10	<10	60	<10	335	4
84737	3.3	0.54	107	156	<0.5	<5	8.16	9	27	10	79	5.58	<1	0.39	<10	2.04	2749	<2	0.01	11	1768	294	2.53	<5	11	457		<0.01	<10	<10	28	11	775	3
84738	3.0	0.39	89	143	<0.5	<5	10.64	9	22	11	49	5.19	<1	0.29	<10	1.69	2765	2	0.01	9	1537	44	2.62	<5	9	444		<0.01	<10	<10	21	12	808	2
84739	1.4	0.58	86	137	<0.5	<5	7.87	1	25	9	76	5.53	<1	0.37	<10	1.13	1920	<2	0.01	11	1687	41	>5.00	<5	7	197		<0.01	<10	<10	26	<10	112	3
84740	1.4	1.21	74	140	<0.5	<5	7.34	3	24	26	46	4.92	<1	0.34	<10	1.92	2532	<2	0.01	10	1559	74	2.27	<5	8	229		<0.01	<10	<10	61	<10	364	2
84741	1.0	1.20	107	141	<0.5	<5	7.37	2	25	25	40	5.38	<1	0.32	<10	1.74	2606	<2	0.01	11	1558	57	3.36	<5	6	242		<0.01	<10	<10	62	<10	191	3
84742	0.6	2.58	80	105	<0.5	<5	7.33	<1	28	24	42	5.84	<1	0.27	<10	2.33	2542	<2	0.01	12	1751	71	3.10	<5	7	196		0.01	<10	<10	116	<10	99	3
84743	0.3	1.16	70	187	<0.5	<5	4.09	3	8	19	31	2.84	<1	0.25	10	0.67	1560	5	0.01	1	1057	22	0.82	<5	2	183		<0.01	<10	<10	34	<10	247	2
84744	<0.2	1.25	22	199	<0.5	<5	2.64	<1	9	23	10	2.91	<1	0.27	<10	0.73	1205	<2	0.01	1	1096	12	0.66	<5	2	95		<0.01	<10	<10	32	<10	100	3
84745	0.8	1.47	128	177	<0.5	<5	5.73	2	15	23	35	3.94	<1	0.26	<10	0.97	2298	<2	0.01	5	1210	37	1.87	<5	3	154		<0.01	<10	<10	48	<10	127	3
84746	1.7	1.66	215	97	<0.5	<5	9.06	3	23	21	49	5.06	<1	0.31	<10	1.17	3438	<2	0.01	10	1559	25	3.74	<5	6	168		<0.01	<10	<10	52	<10	67	3
84747	8.9	1.27	3513	105	0.5	5	12.21	54	29	11	40	7.57	<1	0.28	<10	1.10	5712	<2	0.01	20	1975	188	>5.00	34	5	223		0.01	<10	18	46	<10	130	4
84748	31.3	0.92	4542	46	<0.5	6	>15.00	72	6	10	96	2.94	<1	0.04	<10	1.14	9944	<2	0.01	5	424	186	2.41	44	7	615		<0.01	<10	48	43	<10	138	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2698RJ**

Date : Aug-15-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 13

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84749	1.4	2.24	106	155	<0.5	<5	3.90	1	21	4	60	4.96	<1	0.32	<10	1.58	2514	<2	0.01	3	1557	17	1.61	<5	3	103	0.01	<10	<10	51	<10	90	3	
84750	>200.0	0.60	594	183	<0.5	111	0.50	17	7	20	7466	2.13	6	0.15	<10	0.55	287	583	0.03	4	638	956	1.27	1676	2	86	0.06	<10	<10	24	<10	1014	2	
84751	3.1	1.85	823	159	<0.5	<5	4.81	12	19	5	65	4.30	<1	0.33	<10	1.22	2507	<2	0.01	4	1446	31	1.58	7	3	110	<0.01	<10	<10	39	<10	84	2	
84752	3.5	1.09	2064	112	<0.5	<5	9.36	34	24	19	67	5.21	<1	0.31	<10	0.71	3925	<2	0.01	11	1576	35	>5.00	35	4	233	<0.01	<10	<10	37	<10	46	3	
84753	3.0	1.08	424	90	<0.5	<5	9.81	6	22	18	83	4.63	<1	0.26	<10	0.81	3679	<2	0.01	10	1557	21	4.71	7	4	232	<0.01	<10	<10	42	<10	30	2	
84754	3.1	0.81	827	97	<0.5	<5	11.91	12	22	18	68	4.38	<1	0.24	<10	0.59	3750	<2	0.01	10	1416	27	4.61	13	3	250	<0.01	<10	<10	34	<10	28	2	
84755	3.4	0.87	2060	104	<0.5	<5	8.90	33	23	20	78	5.27	<1	0.30	<10	0.58	3233	<2	0.01	11	1688	37	>5.00	30	4	202	<0.01	<10	<10	31	<10	51	2	
84756	1.6	2.01	764	135	<0.5	<5	8.27	12	27	31	49	5.61	<1	0.25	<10	1.63	3077	<2	0.01	13	1597	85	3.64	9	6	211	<0.01	<10	<10	89	<10	149	3	
84757	1.6	1.27	268	83	<0.5	<5	3.67	11	17	18	71	3.70	<1	0.20	<10	0.99	1500	<2	0.01	7	1016	234	2.43	<5	3	95	<0.01	<10	<10	49	10	765	2	
84758	2.1	1.80	1305	105	<0.5	<5	7.43	22	26	59	67	6.37	<1	0.23	<10	1.58	2509	3	0.01	15	1420	282	>5.00	6	6	176	<0.01	<10	<10	77	<10	356	3	
84759	1.7	1.15	336	137	<0.5	<5	10.27	5	21	32	37	4.91	<1	0.25	<10	1.02	3094	4	0.01	11	1327	123	4.22	<5	5	286	<0.01	<10	<10	48	<10	89	2	
84760	1.3	2.01	650	99	<0.5	<5	7.58	10	27	38	70	5.85	<1	0.23	<10	2.22	2640	<2	0.01	13	1534	89	3.13	<5	7	222	<0.01	<10	<10	83	<10	206	3	
84761	1.7	0.89	338	72	<0.5	<5	5.64	8	34	42	79	6.51	<1	0.37	<10	1.45	2085	<2	0.02	25	1690	206	>5.00	7	7	190	<0.01	<10	<10	51	<10	377	3	
84762	1.0	2.46	101	309	<0.5	<5	7.03	5	34	184	135	6.47	<1	0.15	<10	3.29	2871	<2	0.02	31	1736	129	0.91	<5	19	264	<0.01	<10	<10	179	<10	468	3	
84763	1.4	0.84	182	180	<0.5	<5	8.84	3	26	31	67	5.15	<1	0.37	<10	1.62	2498	<2	0.01	14	1602	50	3.29	<5	7	287	<0.01	<10	<10	43	<10	111	3	
84764	1.5	0.94	123	167	<0.5	<5	8.43	2	28	30	72	5.86	<1	0.32	<10	1.85	2326	2	0.01	14	1645	60	3.50	<5	7	237	<0.01	<10	<10	49	<10	102	3	
84765	0.8	0.85	38	244	<0.5	<5	8.34	<1	25	28	66	5.50	<1	0.29	<10	2.10	2304	<2	0.01	13	1674	45	1.69	<5	8	267	<0.01	<10	<10	62	<10	123	3	
84766	1.3	1.32	70	155	<0.5	<5	8.95	1	28	32	81	5.55	<1	0.29	<10	1.86	2403	<2	0.01	14	1725	19	2.88	<5	7	220	<0.01	<10	<10	61	<10	87	3	
84767	2.3	0.65	256	156	<0.5	<5	8.23	4	25	36	143	4.56	<1	0.36	<10	1.07	2389	2	0.01	13	1523	22	4.52	6	5	209	<0.01	<10	<10	29	<10	116	2	
84768	1.3	1.95	121	137	<0.5	<5	9.71	2	26	37	78	5.47	<1	0.30	<10	1.97	2514	<2	0.01	13	1690	19	2.89	<5	7	200	<0.01	<10	<10	65	<10	131	3	
84769	1.1	1.44	58	144	<0.5	<5	8.65	1	27	40	73	5.33	<1	0.28	<10	2.20	2053	<2	0.01	14	1599	18	1.77	<5	8	208	<0.01	<10	<10	57	<10	100	2	
84794	1.1	1.26	37	118	<0.5	<5	2.31	1	10	87	27	3.31	<1	0.26	<10	0.64	1146	4	0.01	3	924	77	0.64	<5	3	70	<0.01	<10	<10	45	<10	119	2	
84795	0.8	1.26	35	135	<0.5	<5	3.87	1	8	70	13	3.25	<1	0.26	<10	0.65	1346	7	0.02	2	961	21	0.65	<5	4	118	0.01	<10	<10	45	<10	99	2	
84796	9.1	0.85	363	69	<0.5	<5	2.65	38	9	57	186	4.59	<1	0.13	<10	0.58	1656	2	0.01	2	602	2913	3.78	<5	2	52	<0.01	<10	<10	26	49	4120	2	
84797	10.3	1.01	653	56	<0.5	<5	0.99	45	10	77	116	6.90	<1	0.15	<10	0.74	1781	17	0.01	3	701	753	>5.00	<5	2	34	<0.01	<10	<10	34	55	4792	3	
84798	2.7	2.07	253	104	<0.5	<5	3.02	6	13	36	131	6.35	<1	0.19	<10	1.39	3343	17	0.01	2	1156	164	2.58	<5	4	123	0.02	<10	10	79	<10	388	3	
84799	4.1	1.05	265	132	<0.5	<5	4.06	5	14	47	213	4.92	<1	0.32	<10	1.02	3016	45	0.01	2	1254	69	2.07	<5	4	280	0.01	<10	<10	44	<10	225	2	
84800	>200.0	0.85	2288	103	<0.5	51	4.40	38	66	22	2353	3.13	<1	0.09	<10	0.25	954	150	0.05	25	1048	421	0.72	420	2	152	0.04	<10	<10	23	26	351	8	
84801	2.9	1.27	74	187	0.6	<5	4.09	2	18	19	147	5.03	<1	0.64	<10	0.93	2402	22	0.01	2	1440	24	0.77	<5	5	256	0.07	<10	<10	42	<10	158	2	
84802	2.7	1.63	94	139	<0.5	<5	5.17	2	17	23	95	5.61	<1	0.46	<10	1.16	3446	30	0.01	3	1530	73	1.59	<5	6	267	0.03	<10	<10	59	<10	179	3	

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2698RJ**

Date : Aug-15-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 13

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84803	19.4	1.38	365	94	<0.5	<5	7.27	18	15	12	132	5.60	<1	0.25	<10	0.90	3740	12	0.01	2	1476	1958	4.65	<5	4	189	0.01	<10	<10	76	24	1988	3	
84804	11.6	0.88	492	100	<0.5	5	9.15	35	14	40	127	6.30	<1	0.21	<10	0.53	4652	16	0.01	3	1082	2901	>5.00	<5	3	247	0.01	<10	<10	49	54	4298	3	
84805	6.1	1.04	196	124	<0.5	<5	4.61	6	12	43	116	4.32	<1	0.22	<10	0.65	3212	15	0.01	3	1143	267	3.35	<5	3	85	0.03	<10	<10	50	<10	627	2	
84806	<0.2	1.08	<5	237	<0.5	<5	2.36	<1	10	60	3	2.21	<1	0.31	15	0.66	720	<2	0.04	5	910	29	0.23	<5	3	65	0.01	<10	<10	32	<10	67	11	
84807	1.8	1.93	60	195	<0.5	<5	9.06	1	26	188	262	5.82	<1	0.34	<10	1.40	3619	22	0.03	29	1485	58	1.91	<5	20	197	0.06	<10	<10	170	<10	223	5	
84808	3.2	2.58	100	129	0.5	<5	11.70	4	28	193	287	6.65	<1	0.19	<10	2.13	4722	30	0.02	27	1532	68	1.78	<5	21	348	0.04	<10	10	169	<10	430	4	
84809	1.6	2.05	108	46	<0.5	<5	7.06	3	18	167	75	4.82	<1	0.06	<10	1.89	3761	138	0.01	21	1005	101	1.21	<5	14	253	0.01	<10	<10	118	<10	290	2	
84810	1.9	2.31	31	244	0.7	<5	7.81	2	24	247	93	4.64	<1	0.08	<10	2.46	4051	68	0.01	28	1585	138	0.39	<5	23	289	0.04	<10	<10	171	<10	294	4	
84811	4.5	1.85	137	81	0.6	<5	9.79	18	18	136	146	4.90	<1	0.08	<10	1.78	4957	64	0.01	19	1182	659	1.28	<5	14	378	0.01	<10	10	112	28	2140	3	
84812	39.4	0.58	672	26	<0.5	<5	4.01	94	14	44	1268	7.39	<1	0.10	<10	0.48	1790	48	0.01	3	685	>10000	>5.00	31	3	123	<0.01	<10	<10	28	146	>10000	4	
84813	3.8	1.72	77	94	<0.5	<5	5.00	11	20	135	468	4.81	<1	0.11	<10	1.26	3433	123	0.01	19	1331	599	1.41	<5	14	162	0.02	<10	<10	125	16	1246	4	
84814	0.7	1.26	82	171	<0.5	<5	2.51	1	8	49	15	3.30	<1	0.25	<10	0.83	1724	3	0.01	2	960	271	1.00	<5	3	83	<0.01	<10	<10	49	<10	143	4	
84815	0.9	1.20	27	103	<0.5	<5	2.82	<1	8	26	23	2.93	<1	0.33	<10	0.76	1795	3	0.01	2	974	347	0.58	<5	3	122	<0.01	<10	<10	35	<10	89	4	
84816	0.8	1.37	39	157	<0.5	<5	2.84	<1	13	49	162	3.10	<1	0.33	<10	0.76	1168	2	0.02	2	1029	54	0.87	<5	4	108	0.01	<10	<10	48	<10	84	4	
84817	<0.2	0.99	<5	991	<0.5	<5	2.97	<1	8	28	4	1.20	<1	0.31	12	0.68	638	<2	0.03	5	788	13	0.18	<5	3	117	<0.01	<10	<10	22	<10	39	5	
84818	0.3	2.15	37	321	1.1	<5	11.98	<1	21	146	41	7.19	<1	0.25	10	1.84	3244	3	0.03	19	1044	86	0.21	<5	15	310	0.08	<10	<10	110	<10	123	9	
84819	<0.2	2.01	9	121	1.0	<5	6.63	1	22	185	37	4.84	<1	0.11	<10	1.91	2242	14	0.02	24	1406	32	0.10	<5	17	389	0.07	<10	<10	137	<10	251	6	
84820	<0.2	2.55	12	173	0.7	<5	10.76	1	21	176	30	5.94	<1	0.27	<10	1.78	2754	10	0.05	21	1682	28	0.11	<5	16	207	0.11	<10	<10	140	<10	290	9	
84821	0.8	2.93	19	78	0.9	<5	9.87	3	30	207	124	6.35	<1	0.09	<10	2.47	2807	18	0.01	27	1716	15	0.09	<5	19	267	0.10	<10	<10	165	<10	454	11	
84822	1.1	1.62	31	92	0.5	<5	2.99	2	13	66	124	4.00	<1	0.28	10	0.93	1382	49	0.02	5	1252	23	0.77	<5	5	83	0.01	<10	<10	65	<10	295	3	
84823	1.2	1.43	46	88	<0.5	<5	3.62	1	10	68	98	3.80	<1	0.30	<10	0.78	1652	28	0.01	3	937	37	1.17	<5	4	101	<0.01	<10	<10	46	<10	157	2	
84824	0.8	1.73	26	91	<0.5	<5	3.32	1	11	40	85	4.04	<1	0.29	11	0.96	1651	18	0.02	2	1171	17	0.67	<5	4	152	0.01	<10	<10	60	<10	207	3	
84825	<0.2	1.17	<5	264	0.9	<5	0.67	<1	9	195	2	2.31	<1	0.53	12	0.63	634	2	0.11	8	840	14	0.01	<5	3	72	0.18	<10	<10	42	<10	59	3	
84826	2.0	1.51	81	70	<0.5	<5	6.78	11	10	35	88	3.71	<1	0.20	<10	1.00	2988	18	0.01	2	1006	146	1.18	<5	3	163	<0.01	<10	<10	49	15	1173	2	
84827	0.7	1.59	82	112	<0.5	<5	2.30	2	11	81	54	4.06	<1	0.28	10	1.04	1752	22	0.01	3	1146	48	1.30	<5	4	103	<0.01	<10	<10	54	<10	205	2	
84828	0.6	1.66	44	91	<0.5	<5	2.79	2	11	40	75	4.36	<1	0.21	11	1.04	1778	24	0.02	2	1192	21	1.07	<5	5	119	0.01	<10	<10	67	<10	234	3	
84829	0.7	1.85	31	102	<0.5	<5	3.25	1	11	52	69	4.18	<1	0.27	10	1.15	1758	28	0.02	2	1159	49	0.60	<5	5	182	0.01	<10	<10	61	<10	186	3	
84830	2.1	1.31	29	74	0.8	<5	4.30	1	25	142	402	3.34	<1	0.11	<10	1.01	1573	46	0.05	22	1727	25	0.40	<5	7	97	0.20	<10	<10	91	<10	183	4	
84831	1.5	2.25	45	84	0.8	<5	13.13	2	27	186	103	5.45	<1	0.15	<10	1.71	4271	35	0.03	25	1489	35	0.44	<5	18	391	0.09	<10	<10	147	<10	239	6	
84832	2.0	1.62	43	52	0.7	<5	7.87	2	23	156	139	4.11	<1	0.07	<10	1.43	2330	46	0.02	21	1719	61	0.47	<5	12	293	0.10	<10	<10	109	<10	229	7	

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

Ascot Resources Ltd

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Report No : 8V2698RJ

Attention: Sue Deane

Tel: (604) 327-3436 Fax: (604) 327-3423

Date : Aug-15-08

Project: Dilworth/Shipment 13

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84833	0.2	0.79	45	76	<0.5	<5	2.46	<1	8	71	10	2.82	1	0.20	<10	0.62	1294	4	0.02	2	738	12	0.58	<5	4	129	<0.01	<10	<10	26	<10	44	2	
84834	0.5	0.75	109	101	<0.5	<5	3.02	2	8	63	12	3.17	<1	0.20	<10	0.56	1677	4	0.02	2	799	35	0.92	<5	4	161	<0.01	<10	<10	24	<10	127	2	
84835	1.5	0.40	122	127	<0.5	<5	3.33	3	7	38	15	2.94	<1	0.29	<10	0.40	1741	3	0.01	1	946	189	1.04	<5	2	199	<0.01	<10	<10	8	<10	242	4	
84836	0.8	0.61	63	84	<0.5	<5	2.76	1	7	86	8	2.94	<1	0.23	<10	0.58	1400	2	0.02	2	763	14	0.71	<5	3	202	<0.01	<10	<10	18	<10	60	2	
84837	0.8	0.48	86	81	<0.5	<5	2.60	1	8	77	12	2.67	<1	0.24	<10	0.51	1387	5	0.01	2	792	14	0.68	<5	3	176	<0.01	<10	<10	13	<10	59	2	
84838	1.8	0.52	260	87	<0.5	<5	3.78	4	12	54	57	3.23	<1	0.26	<10	0.65	1730	4	0.01	3	919	30	0.63	<5	4	255	<0.01	<10	<10	17	<10	70	2	
84839	1.0	0.90	102	57	<0.5	<5	5.31	1	7	79	47	2.69	<1	0.16	<10	0.48	2022	7	0.01	2	634	21	0.77	<5	2	87	<0.01	<10	<10	31	<10	42	1	
84840	10.3	0.92	248	49	<0.5	<5	12.78	4	7	28	68	2.83	<1	0.14	<10	0.48	4062	4	0.01	2	762	87	1.24	<5	2	203	<0.01	<10	<10	39	<10	127	1	
84841	0.9	1.08	80	82	<0.5	<5	2.47	1	10	58	49	3.22	<1	0.22	<10	0.55	1354	8	0.01	1	885	13	0.84	<5	2	71	0.02	<10	<10	40	<10	62	2	
84842	<0.2	1.38	15	74	<0.5	<5	2.81	<1	11	34	10	3.45	<1	0.21	<10	0.77	1145	5	0.02	1	987	5	0.24	<5	3	79	0.05	<10	<10	54	<10	80	2	
84843	0.8	0.77	85	75	<0.5	<5	2.42	1	12	59	50	3.07	<1	0.26	<10	0.71	1265	7	0.01	1	879	18	0.62	<5	3	198	<0.01	<10	<10	22	<10	52	1	
84844	0.9	0.84	87	66	<0.5	<5	3.01	1	10	67	67	2.67	<1	0.21	<10	0.50	1516	8	0.02	2	723	10	0.58	<5	2	99	<0.01	<10	<10	30	<10	53	1	
84845	0.4	0.95	40	77	<0.5	<5	2.08	<1	10	69	79	3.08	<1	0.28	<10	0.72	792	7	0.02	2	870	9	0.45	<5	2	91	<0.01	<10	<10	29	<10	70	1	
84846	1.6	1.14	91	166	<0.5	<5	2.55	1	10	66	36	3.28	<1	0.21	<10	0.60	1005	3	0.01	2	876	20	0.60	<5	3	63	<0.01	<10	<10	37	<10	78	2	
84847	0.8	1.21	47	71	<0.5	<5	1.70	<1	9	92	35	3.13	<1	0.19	<10	0.69	764	5	0.02	2	893	13	0.50	<5	4	57	<0.01	<10	<10	46	<10	67	2	
84848	<0.2	1.20	35	73	<0.5	<5	1.88	<1	8	77	10	3.08	<1	0.23	<10	0.62	820	<2	0.02	2	994	9	0.42	<5	3	62	<0.01	<10	<10	37	<10	53	2	
84849	0.6	1.31	63	66	<0.5	<5	2.47	<1	9	67	25	3.33	<1	0.22	<10	0.70	1345	5	0.01	2	900	10	0.68	<5	3	85	<0.01	<10	<10	42	<10	58	2	
84850	<0.2	0.99	<5	235	0.8	<5	0.49	<1	8	125	<1	2.02	<1	0.49	<10	0.58	566	<2	0.08	6	785	5	<0.01	<5	2	54	0.15	<10	<10	38	<10	48	2	
84851	0.3	1.51	67	84	<0.5	<5	2.35	1	12	66	21	3.81	<1	0.25	<10	0.92	1355	4	0.01	4	909	9	0.95	<5	4	106	<0.01	<10	<10	54	<10	92	2	
84852	0.5	1.21	55	83	<0.5	<5	4.22	1	11	57	29	3.19	<1	0.24	<10	0.62	1711	3	0.01	2	941	13	0.86	<5	3	114	<0.01	<10	<10	42	<10	71	2	
84853	0.6	1.30	38	68	<0.5	<5	3.63	1	11	53	69	3.39	<1	0.24	<10	0.59	1586	4	0.01	2	966	33	0.56	<5	3	101	0.01	<10	<10	56	<10	181	2	
84854	0.4	1.09	48	73	<0.5	<5	2.85	<1	8	73	11	3.02	<1	0.25	<10	0.64	1392	2	0.01	2	804	11	0.65	<5	3	98	<0.01	<10	<10	31	<10	70	2	
84855	1.1	0.82	78	66	<0.5	<5	6.40	1	9	57	16	2.98	<1	0.25	<10	0.57	2294	4	0.01	2	858	11	1.04	<5	3	223	<0.01	<10	<10	22	<10	94	2	
84856	0.7	1.01	73	72	<0.5	<5	1.48	1	8	87	13	3.05	<1	0.21	<10	0.55	1136	2	0.01	2	685	8	0.95	<5	2	45	<0.01	<10	<10	32	<10	68	2	
84857	1.5	0.73	94	72	<0.5	<5	2.49	2	6	105	23	2.52	<1	0.17	<10	0.43	1382	4	0.01	3	469	53	1.09	<5	2	68	<0.01	<10	<10	22	<10	89	1	
84858	4.9	1.66	320	95	<0.5	<5	0.55	17	13	61	73	6.89	<1	0.17	<10	1.26	1981	6	0.01	2	972	1323	4.44	<5	3	18	<0.01	<10	<10	68	14	1655	3	
84859	9.8	0.67	525	53	<0.5	<5	2.30	87	10	75	234	7.70	<1	0.13	<10	0.49	1661	6	0.01	1	704	3601	>5.00	<5	1	44	<0.01	<10	<10	28	84	9899	3	
84860	10.0	1.03	265	116	<0.5	<5	1.37	42	10	92	212	5.33	<1	0.13	<10	0.76	2323	4	0.01	2	687	4722	4.16	<5	2	45	<0.01	<10	<10	54	41	5032	2	
84861	27.7	1.11	650	50	<0.5	<5	2.42	73	15	53	1777	9.73	<1	0.15	<10	0.78	2089	<2	0.01	3	886	2217	>5.00	<5	2	66	<0.01	<10	10	47	57	7318	4	
84862	29.8	0.59	1371	35	<0.5	<5	2.62	148	11	84	2061	13.53	<1	0.09	<10	0.45	1535	<2	0.01	1	513	3994	>5.00	<5	1	56	<0.01	<10	10	15	145	>10000	5	

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2698RJ**

Date : Aug-15-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 13

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84863	9.5	1.44	994	54	<0.5	5	1.54	61	11	83	329	10.96	<1	0.11	<10	1.00	2026	6	0.01	2	556	1695	>5.00	<5	2	32	<0.01	<10	11	34	46	5740	4	
84864	5.2	2.26	523	64	<0.5	<5	0.33	57	11	64	160	10.23	<1	0.18	<10	1.64	2503	10	0.01	2	777	887	>5.00	<5	3	11	<0.01	<10	14	49	48	6051	4	
84865	5.7	1.61	226	76	<0.5	<5	1.03	6	8	85	136	6.57	<1	0.18	<10	1.21	2233	5	0.01	2	734	3599	4.14	<5	3	36	<0.01	<10	10	48	<10	332	2	
84893A	0.2	0.97	47	98	<0.5	<5	2.33	1	9	112	10	3.56	<1	0.20	<10	0.64	1422	3	0.02	2	686	30	0.76	<5	3	69	<0.01	<10	<10	33	<10	108	2	
84894	<0.2	0.78	22	155	<0.5	<5	2.10	<1	9	101	4	3.70	<1	0.25	<10	0.62	1207	3	0.02	2	798	19	0.54	<5	5	126	<0.01	<10	<10	21	<10	71	2	
84895	0.3	0.68	37	106	<0.5	<5	2.13	1	8	111	10	3.44	<1	0.22	<10	0.58	1527	2	0.02	2	724	67	0.67	<5	4	91	<0.01	<10	<10	18	<10	111	2	
84896	0.2	0.41	64	104	<0.5	<5	3.31	1	9	109	3	3.76	<1	0.23	<10	0.66	1791	5	0.02	2	719	13	0.99	<5	4	234	<0.01	<10	<10	11	<10	49	2	
84897	0.3	0.52	57	122	<0.5	<5	3.45	1	8	49	8	3.43	<1	0.32	<10	0.65	1755	<2	0.01	1	883	18	0.75	<5	3	243	<0.01	<10	<10	10	<10	87	3	
84898	0.2	0.57	62	112	<0.5	<5	3.26	1	8	72	8	3.50	<1	0.33	<10	0.74	1592	2	0.02	1	839	17	0.59	<5	4	224	<0.01	<10	<10	14	<10	94	3	
84899	<0.2	0.55	27	91	<0.5	<5	2.60	<1	9	102	8	3.49	<1	0.27	<10	0.72	1183	6	0.02	2	776	10	0.48	<5	5	181	<0.01	<10	<10	17	<10	58	2	
84900	<0.2	1.04	<5	279	0.8	<5	0.54	<1	9	160	<1	2.32	<1	0.53	10	0.64	656	2	0.07	6	780	5	<0.01	<5	3	55	0.14	<10	<10	44	<10	58	2	
84901	1.0	1.13	57	90	<0.5	<5	2.31	1	10	85	15	3.94	<1	0.21	<10	0.77	1284	3	0.02	2	786	62	0.98	<5	4	89	<0.01	<10	<10	37	<10	118	2	
84902	<0.2	1.41	50	90	<0.5	<5	3.23	1	17	68	47	4.48	<1	0.21	<10	0.63	1370	4	0.02	2	881	8	0.67	<5	5	118	0.01	<10	<10	84	<10	65	2	
84903	0.7	1.54	75	82	0.5	<5	3.14	1	19	48	123	4.75	<1	0.26	<10	0.66	1277	5	0.02	2	944	9	1.04	<5	4	83	0.06	<10	<10	84	<10	75	3	
84904	1.1	1.50	134	92	<0.5	<5	2.80	3	18	56	151	5.09	<1	0.23	<10	0.70	1480	5	0.02	2	1038	11	1.51	<5	5	83	0.02	<10	<10	86	<10	107	3	
84905	0.4	1.48	38	65	<0.5	<5	2.27	1	15	47	47	4.36	<1	0.20	<10	1.04	1604	4	0.01	4	646	14	0.69	<5	5	72	<0.01	<10	<10	74	<10	88	2	
84906	0.7	0.86	150	115	<0.5	<5	2.95	3	20	69	37	5.20	<1	0.26	<10	0.54	1528	5	0.01	4	953	30	2.30	<5	5	112	<0.01	<10	<10	39	<10	78	2	
84907	<0.2	1.51	22	75	<0.5	<5	2.77	<1	13	47	50	4.04	<1	0.18	<10	0.94	1241	3	0.02	2	893	10	0.45	<5	4	75	0.04	<10	<10	63	<10	79	2	
84907A	0.6	1.23	56	63	<0.5	<5	3.35	<1	10	66	46	3.04	<1	0.15	<10	0.69	1407	4	0.01	1	810	11	0.66	<5	3	85	<0.01	<10	<10	47	<10	56	2	
84908	0.2	1.29	11	80	0.5	<5	3.61	<1	11	64	33	3.07	<1	0.20	<10	0.74	1315	3	0.02	2	846	5	0.29	<5	4	120	0.05	<10	<10	46	<10	57	2	
84909	0.3	1.42	28	92	<0.5	<5	3.98	<1	13	58	38	3.54	<1	0.18	<10	0.71	1539	3	0.02	2	926	9	0.40	<5	4	97	0.02	<10	<10	58	<10	113	2	
84910	0.2	1.37	19	95	<0.5	<5	3.64	<1	11	54	55	3.38	<1	0.21	<10	0.68	1363	2	0.02	1	961	7	0.43	<5	3	116	<0.01	<10	<10	55	<10	69	2	
84911	0.3	1.28	43	71	<0.5	<5	3.13	<1	9	77	33	3.18	<1	0.18	<10	0.75	1299	6	0.02	1	838	12	0.62	<5	3	92	<0.01	<10	<10	51	<10	59	2	
84912	<0.2	1.23	29	103	<0.5	<5	3.28	<1	9	67	15	3.03	<1	0.19	<10	0.75	1214	3	0.02	2	848	6	0.71	<5	4	78	0.01	<10	<10	47	<10	53	2	
84913	0.9	1.13	104	84	<0.5	<5	4.03	1	10	58	64	3.52	<1	0.21	<10	0.70	1694	6	0.01	1	898	24	1.24	<5	3	103	0.01	<10	<10	50	<10	58	2	
84914	0.7	1.46	27	77	<0.5	<5	3.35	<1	11	74	88	3.77	<1	0.21	<10	0.72	1453	3	0.02	2	985	24	0.61	<5	4	91	0.02	<10	<10	58	<10	83	2	
84915	0.3	0.99	38	65	<0.5	<5	2.03	<1	8	95	39	2.69	<1	0.19	<10	0.52	944	5	0.01	2	717	7	0.68	<5	2	53	0.01	<10	<10	34	<10	47	2	
84916	0.2	1.28	21	70	<0.5	<5	4.69	<1	9	65	23	3.13	<1	0.19	<10	0.68	1672	2	0.02	2	910	21	0.39	<5	4	107	0.01	<10	<10	46	<10	67	2	
84917	0.3	0.92	34	75	<0.5	<5	4.41	<1	7	84	16	2.44	<1	0.21	<10	0.49	1566	4	0.01	2	708	6	0.54	<5	2	134	<0.01	<10	<10	28	<10	38	2	
84918	0.2	1.19	57	76	<0.5	<5	3.33	<1	7	70	18	2.91	<1	0.19	<10	0.69	1333	4	0.02	2	782	7	0.35	<5	3	137	<0.01	<10	<10	39	<10	47	2	

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2698RJ**

Date : Aug-15-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 13

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84919	<0.2	1.15	19	66	<0.5	<5	2.47	<1	7	82	13	2.84	<1	0.16	<10	0.65	962	2	0.02	1	738	6	0.42	<5	3	82	0.01	<10	<10	40	<10	46	2	
84920	0.4	0.77	52	413	<0.5	<5	4.19	<1	6	82	12	2.61	<1	0.20	<10	0.46	1504	6	0.01	2	672	12	0.74	<5	3	213	<0.01	<10	<10	17	<10	44	2	
84921	1.0	0.64	74	293	<0.5	<5	2.90	2	8	81	23	3.17	<1	0.23	<10	0.50	1518	8	0.01	2	798	206	1.03	<5	3	198	<0.01	<10	<10	10	<10	208	2	
84922	1.0	0.99	59	370	<0.5	<5	5.43	1	8	61	18	2.82	<1	0.25	<10	0.53	1767	5	0.01	2	778	14	0.83	<5	3	374	<0.01	<10	<10	14	<10	87	2	
84923	1.4	1.30	21	260	<0.5	<5	3.41	<1	9	65	131	3.03	<1	0.27	<10	0.57	1436	4	0.01	2	931	8	0.30	<5	2	154	<0.01	<10	<10	33	<10	149	2	
84924	2.0	1.38	26	114	<0.5	<5	4.17	<1	9	45	204	3.20	<1	0.29	<10	0.54	1608	8	0.01	2	1034	16	0.40	<5	2	181	<0.01	<10	<10	39	<10	98	2	
84925	>200.0	0.85	470	195	<0.5	98	0.47	15	7	246	6385	2.09	5	0.28	<10	0.50	291	486	0.08	7	526	783	1.03	1264	2	77	0.05	<10	<10	27	<10	782	2	
84926	2.9	1.27	51	121	<0.5	<5	3.48	1	9	45	115	3.29	<1	0.28	<10	0.56	1715	10	0.01	2	942	53	0.72	<5	2	117	<0.01	<10	<10	35	<10	89	2	
84927	3.8	0.89	38	113	<0.5	<5	2.80	<1	9	85	75	2.82	<1	0.24	<10	0.41	1228	21	0.01	2	777	19	0.75	6	2	123	<0.01	<10	<10	30	<10	50	2	
84928	2.5	1.43	210	162	<0.5	<5	3.52	4	15	43	84	4.72	<1	0.21	<10	1.02	1760	6	0.01	1	1056	100	1.74	<5	4	154	<0.01	<10	<10	68	<10	297	2	
84929	0.8	1.66	38	74	<0.5	<5	2.89	<1	14	51	59	3.87	<1	0.25	<10	1.14	1656	5	0.01	1	1096	19	0.48	<5	4	148	<0.01	<10	<10	65	<10	94	2	
84930	0.9	0.69	40	68	<0.5	<5	3.66	<1	10	59	26	3.34	<1	0.29	<10	0.88	1660	15	0.01	2	836	21	0.74	<5	4	187	<0.01	<10	<10	20	<10	81	2	
84931	0.7	1.19	37	91	<0.5	<5	2.92	<1	9	80	28	2.93	<1	0.24	<10	0.69	1439	9	0.01	2	873	13	0.73	<5	3	152	<0.01	<10	<10	38	<10	105	2	
84932	0.8	1.20	96	85	<0.5	<5	2.25	1	9	78	40	3.47	<1	0.22	<10	0.75	1497	6	0.01	2	874	22	1.44	<5	3	111	<0.01	<10	<10	39	<10	92	2	
84933	1.3	1.02	96	89	<0.5	<5	2.73	2	9	50	34	3.37	<1	0.26	<10	0.55	1791	4	0.01	1	976	76	1.76	<5	2	119	<0.01	<10	<10	25	<10	216	3	
84934	5.8	0.76	95	114	<0.5	<5	2.76	13	9	52	162	3.42	<1	0.33	<10	0.57	1684	3	0.01	2	948	1222	1.77	<5	3	148	0.01	<10	<10	15	15	1452	2	
84935	1.0	0.56	66	64	<0.5	<5	2.77	1	7	84	42	2.38	<1	0.20	<10	0.46	1724	4	0.01	2	660	60	1.07	<5	2	84	<0.01	<10	<10	15	<10	106	1	
84936	4.7	0.47	165	68	<0.5	<5	5.85	8	7	64	120	3.19	<1	0.16	<10	0.39	2496	4	0.01	2	713	570	2.71	<5	2	251	<0.01	<10	<10	15	<10	713	2	
139171	3.8	0.78	93	110	<0.5	<5	0.47	1	7	53	19	4.59	<1	0.23	<10	0.36	456	8	0.01	1	858	79	3.06	6	3	16	0.02	<10	<10	22	<10	72	3	
139172	19.7	0.37	134	46	<0.5	<5	0.17	15	10	91	44	6.84	<1	0.19	<10	0.12	302	<2	0.01	2	867	1680	>5.00	9	1	8	0.01	<10	<10	14	23	2037	4	
139173	9.6	0.57	60	136	<0.5	<5	0.13	4	9	92	12	4.40	<1	0.18	<10	0.27	823	2	0.01	2	792	481	2.20	<5	2	8	<0.01	<10	<10	18	<10	637	2	
139174	36.1	0.30	77	155	<0.5	<5	<0.01	2	3	94	11	3.63	<1	0.21	<10	0.05	93	6	0.01	1	581	919	1.55	22	1	1	<0.01	<10	<10	10	<10	309	2	
139175	5.0	0.20	106	226	<0.5	<5	<0.01	3	2	126	7	4.89	1	0.20	<10	0.02	70	3	0.01	1	695	1026	1.17	6	1	9	<0.01	<10	<10	10	<10	586	2	
139176	9.1	0.58	58	159	<0.5	<5	0.06	5	6	94	10	4.31	<1	0.22	<10	0.27	399	<2	0.01	2	886	556	1.84	<5	2	6	<0.01	<10	<10	22	10	786	2	
139177	127.0	0.53	57	156	<0.5	<5	0.02	1	4	106	12	4.39	3	0.19	<10	0.24	355	2	0.02	1	942	1267	0.94	18	2	6	<0.01	<10	<10	25	<10	173	2	
139178	0.9	0.41	125	259	<0.5	<5	0.01	2	6	91	21	3.49	<1	0.23	<10	0.09	371	5	0.01	2	838	189	0.61	<5	2	4	<0.01	<10	<10	16	<10	158	2	
139179	2.9	0.41	111	94	<0.5	<5	0.06	5	11	101	16	5.15	<1	0.27	<10	0.11	460	3	0.01	2	920	859	3.16	<5	2	6	<0.01	<10	<10	17	10	857	3	
139180	1.5	0.40	69	198	<0.5	<5	0.07	1	8	84	18	4.10	<1	0.27	<10	0.10	422	<2	0.01	2	1034	206	1.65	5	2	8	<0.01	<10	<10	15	<10	320	2	
139181	2.3	0.28	102	173	<0.5	<5	<0.01	3	5	110	8	3.42	<1	0.23	<10	0.03	126	4	0.01	1	581	513	1.66	5	1	3	<0.01	<10	<10	12	<10	492	2	
139182	1.7	0.22	91	96	<0.5	<5	0.02	3	5	114	24	3.60	<1	0.17	<10	0.03	153	<2	0.01	2	509	533	2.45	7	1	3	<0.01	<10	<10	10	<10	505	2	

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2698RJ**

Date : Aug-15-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 13

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139183	1.3	0.33	95	93	<0.5	<5	0.12	6	10	92	13	4.69	<1	0.25	<10	0.09	343	3	0.01	1	865	531	3.36	<5	2	8	<0.01	<10	<10	14	12	1036	2	
139184	8.1	0.22	184	23	<0.5	7	<0.01	2	6	97	18	10.29	<1	0.18	<10	0.02	70	<2	0.01	<1	499	159	>5.00	<5	1	1	<0.01	<10	<10	9	<10	112	5	
139185	0.9	0.25	89	109	<0.5	<5	0.05	1	8	86	2	2.91	<1	0.17	<10	0.06	200	3	0.01	1	589	63	2.06	<5	1	3	<0.01	<10	<10	11	<10	76	2	
139186	1.6	0.39	79	113	<0.5	<5	0.07	2	9	56	12	4.52	<1	0.27	<10	0.09	449	<2	0.01	1	1049	115	2.38	<5	2	6	<0.01	<10	<10	13	<10	368	2	
139187	2.3	0.48	80	78	<0.5	<5	0.08	6	9	76	14	5.58	<1	0.26	<10	0.19	702	2	0.01	1	984	579	3.73	5	1	6	<0.01	<10	<10	16	13	1131	3	
139188	4.1	0.64	116	88	<0.5	<5	0.10	2	11	78	55	5.45	<1	0.29	<10	0.22	797	6	0.01	2	1083	885	3.75	5	2	6	<0.01	<10	<10	25	<10	228	3	
139189	1.3	1.12	63	191	<0.5	<5	0.18	<1	16	29	71	4.84	<1	0.34	<10	0.53	1433	11	0.01	1	1355	59	1.90	<5	4	10	<0.01	<10	<10	49	<10	129	3	
139190	65.3	0.71	402	180	<0.5	<5	0.02	6	3	83	59	5.46	2	0.24	<10	0.23	294	2	0.01	1	903	>10000	1.08	42	1	8	<0.01	<10	<10	28	<10	141	3	
139191	193.1	0.95	690	155	<0.5	<5	0.03	10	3	48	315	7.43	12	0.25	<10	0.39	650	<2	0.01	<1	1095	7666	0.97	46	1	5	0.01	<10	<10	33	<10	436	4	
139192	141.0	0.23	723	34	<0.5	5	<0.01	17	2	283	101	8.61	18	0.17	<10	0.02	42	2	0.01	6	319	>10000	>5.00	77	<1	1	<0.01	<10	<10	6	12	1064	5	
139193	175.5	0.23	630	113	<0.5	<5	<0.01	10	1	147	120	3.80	14	0.20	<10	0.02	31	<2	0.01	3	326	>10000	1.56	102	<1	2	<0.01	<10	<10	6	<10	198	2	
139194	>200.0	0.55	346	85	<0.5	<5	0.01	14	4	144	176	3.66	3	0.30	<10	0.12	221	<2	0.01	3	699	>10000	3.71	144	1	5	<0.01	<10	<10	15	<10	724	2	
139195	>200.0	0.22	295	87	<0.5	<5	<0.01	23	2	98	118	2.95	7	0.17	<10	0.02	26	<2	0.01	2	403	>10000	3.42	148	<1	6	<0.01	<10	<10	7	17	1794	2	
139196	>200.0	0.14	614	69	<0.5	<5	<0.01	22	1	285	158	3.89	11	0.11	<10	0.01	26	3	0.01	7	155	>10000	3.48	114	<1	6	<0.01	<10	<10	3	13	1241	2	
139197	>200.0	0.07	669	27	<0.5	<5	<0.01	55	2	239	646	6.86	7	0.04	<10	0.01	25	2	0.01	5	256	>10000	>5.00	295	<1	26	<0.01	<10	<10	3	46	4280	3	
139198	>200.0	0.25	412	35	<0.5	<5	<0.01	73	2	260	365	6.65	6	0.19	<10	0.02	83	3	0.01	5	498	>10000	>5.00	224	<1	10	<0.01	<10	<10	7	58	5933	3	
139199	>200.0	0.15	470	63	<0.5	<5	<0.01	10	2	264	143	4.99	26	0.12	<10	0.01	30	<2	0.01	5	225	>10000	2.16	103	<1	2	<0.01	<10	<10	4	<10	432	3	
139200	53.2	0.57	347	119	<0.5	<5	0.02	9	5	281	105	4.94	1	0.28	<10	0.12	112	10	0.01	7	761	3407	2.59	27	1	3	<0.01	<10	<10	13	10	841	3	
139201	17.8	0.64	292	100	<0.5	<5	0.05	4	6	95	55	3.37	<1	0.21	<10	0.28	226	6	0.01	2	992	1412	1.41	10	1	3	<0.01	<10	<10	15	<10	210	2	
139202	90.5	0.37	277	95	<0.5	<5	<0.01	5	3	292	68	2.87	<1	0.20	<10	0.07	65	13	0.01	7	599	1412	0.66	42	1	2	<0.01	<10	<10	9	<10	228	2	
139203	3.9	1.29	288	117	<0.5	<5	0.13	4	12	86	16	3.60	<1	0.21	<10	0.69	1018	12	0.01	2	1256	131	0.58	<5	2	5	0.01	<10	<10	41	<10	85	2	
139204	3.4	1.45	294	134	<0.5	<5	1.01	4	11	77	14	3.99	<1	0.25	<10	0.77	1221	2	0.01	2	1157	75	0.84	<5	2	29	0.03	<10	<10	40	<10	111	2	
139205	5.3	0.87	488	119	<0.5	<5	0.07	7	5	65	10	3.59	<1	0.22	<10	0.39	475	41	0.01	1	1024	81	0.70	5	1	5	0.01	<10	<10	29	<10	69	2	
139206	1.9	1.11	240	119	<0.5	<5	0.11	4	10	70	8	3.72	<1	0.21	<10	0.55	986	4	0.01	2	1081	93	0.76	<5	1	3	0.01	<10	<10	31	<10	163	2	
139207	1.1	1.46	180	127	<0.5	<5	0.16	2	7	40	9	4.17	<1	0.23	<10	0.79	976	<2	0.01	1	1373	73	0.64	<5	2	4	0.02	<10	<10	40	<10	65	2	
139208	3.7	0.53	260	185	<0.5	<5	0.01	4	3	167	7	3.24	<1	0.31	<10	0.12	151	5	0.01	4	774	419	0.59	<5	1	4	0.02	<10	<10	18	<10	109	2	
139209	2.9	0.58	299	128	<0.5	<5	0.14	5	8	72	26	3.59	<1	0.22	<10	0.24	337	9	0.01	2	999	212	0.94	6	1	6	0.04	<10	<10	19	<10	179	3	
139210	4.8	0.40	283	182	<0.5	<5	0.01	4	3	197	9	2.15	<1	0.27	<10	0.08	86	10	0.01	4	627	476	0.32	5	1	7	0.06	<10	<10	8	<10	80	2	
139211	1.9	0.19	188	111	<0.5	<5	<0.01	3	1	144	3	1.29	<1	0.18	<10	0.02	22	4	0.01	3	314	133	0.10	5	<1	5	<0.01	<10	<10	5	<10	15	1	
139212	19.7	0.11	204	61	<0.5	<5	<0.01	6	1	302	15	2.14	1	0.11	<10	0.01	29	4	0.01	8	117	1031	1.26	19	<1	3	<0.01	<10	<10	1	<10	521	1	

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2698RJ**

Date : Aug-15-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 13

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139213	1.0	0.71	177	154	<0.5	<5	0.08	2	4	92	11	2.80	1	0.25	<10	0.30	227	<2	0.01	2	853	31	0.32	<5	1	6	0.06	<10	<10	18	<10	38	2	
139214	<0.2	1.50	134	140	<0.5	<5	0.19	1	18	61	28	5.75	<1	0.29	<10	0.81	513	<2	0.03	3	1646	24	2.37	<5	4	8	0.03	<10	<10	64	11	89	4	
139215	<0.2	2.06	100	236	<0.5	<5	0.18	1	10	23	25	5.84	<1	0.27	<10	1.21	671	<2	0.02	1	1830	17	0.70	<5	4	9	0.02	<10	<10	77	<10	94	4	
139216	<0.2	1.53	246	193	<0.5	<5	0.07	3	6	68	20	5.95	<1	0.37	<10	0.72	373	<2	0.04	1	1812	18	0.63	<5	4	13	0.06	<10	<10	71	<10	42	4	
139217	0.2	1.15	271	130	<0.5	<5	0.09	3	8	23	31	5.50	<1	0.28	<10	0.59	303	<2	0.03	<1	1840	18	1.00	<5	3	17	0.09	<10	<10	52	<10	36	4	
WDR08-04	<0.2	1.81	12	125	1.1	<5	3.66	<1	10	86	39	4.19	<1	0.18	<10	2.47	459	<2	0.03	97	1463	15	0.02	<5	6	505	<0.01	<10	<10	44	<10	107	4	
HL08-23 cuttings	27.0	1.00	668	24	<0.5	7	0.98	101	10	16	98	9.02	<1	0.09	<10	0.81	1362	7	0.01	6	672	>10000	>5.00	<5	2	36	0.01	<10	<10	25	213	>10000	5	
Blank-Inhouse	<0.2	1.14	<5	246	1.0	<5	0.71	<1	10	151	1	2.40	<1	0.48	13	0.65	633	<2	0.11	7	952	43	0.03	<5	3	66	0.19	<10	<10	46	<10	86	3	

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2698RP**

Date : Aug-15-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 13

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84737	2.8	0.45	97	138	<0.5	<5	8.24	9	26	13	74	6.04	<1	0.34	<10	2.07	3098	2	0.01	11	1434	284	2.30	12	10	392	7	<0.01	<10	<10	33	<10	771	4
84738	2.6	0.38	68	141	<0.5	<5	12.01	9	20	13	66	5.46	<1	0.27	<10	1.82	2744	<2	0.01	8	1197	45	2.72	<5	9	434	<5	<0.01	<10	<10	22	<10	815	2
84739	1.2	0.59	75	80	<0.5	<5	9.05	1	24	11	80	6.11	<1	0.37	<10	1.25	1947	<2	0.01	10	1375	43	>5.00	<5	7	193	<5	<0.01	<10	<10	28	<10	123	2
84740	0.9	1.20	57	145	<0.5	<5	8.27	3	22	28	49	5.37	<1	0.32	<10	2.08	2559	<2	0.01	10	1232	76	2.32	<5	8	223	<5	<0.01	<10	<10	63	<10	395	2
84741	0.8	1.18	86	142	<0.5	<5	8.46	2	24	29	45	5.99	<1	0.31	<10	1.93	2664	<2	0.01	10	1253	59	3.55	<5	6	237	<5	<0.01	<10	<10	65	<10	210	2
84742	0.7	2.62	61	109	<0.5	<5	8.36	<1	26	29	47	6.52	<1	0.25	<10	2.52	2654	<2	0.01	11	1358	72	3.09	<5	7	184	<5	<0.01	<10	<10	120	<10	104	2
84743	<0.2	1.24	71	212	<0.5	<5	5.02	3	9	21	36	3.39	<1	0.26	10	0.80	1719	4	0.01	1	919	26	0.92	<5	2	187	<5	<0.01	<10	<10	37	<10	268	2
84744	<0.2	1.29	17	234	<0.5	<5	3.08	<1	10	27	14	3.32	<1	0.28	<10	0.85	1346	<2	0.01	1	894	13	0.73	<5	2	98	<5	<0.01	<10	<10	36	<10	118	2
84745	0.5	1.53	107	111	<0.5	<5	6.87	2	14	27	37	4.60	<1	0.26	<10	1.11	2403	<2	0.01	4	970	39	1.95	<5	3	152	<5	<0.01	<10	<10	52	<10	132	2
84746	1.3	1.69	176	51	<0.5	<5	10.74	3	21	23	51	5.53	<1	0.31	<10	1.30	3372	<2	0.01	8	1209	23	3.72	<5	6	163	<5	<0.01	<10	<10	52	<10	71	2
84747	7.8	1.20	2782	52	<0.5	<5	>15.00	51	26	16	38	8.60	<1	0.23	<10	1.05	5554	<2	0.01	18	1574	173	>5.00	14	5	181	<5	0.01	<10	20	43	<10	144	2
84748	24.1	0.88	2995	43	<0.5	5	>15.00	59	5	12	82	3.15	<1	0.03	<10	1.20	8781	<2	0.01	3	349	158	2.01	23	5	518	<5	<0.01	<10	47	35	<10	134	<1
84749	1.0	2.22	70	160	<0.5	<5	4.22	1	20	6	61	5.41	<1	0.32	<10	1.69	2613	<2	0.01	3	1164	17	1.53	<5	3	87	<5	<0.01	<10	<10	52	<10	95	2
84750	>200.0	0.66	537	215	<0.5	159	0.62	19	9	25	7450	2.55	6	0.17	<10	0.65	333	489	0.03	5	540	1088	1.40	1356	2	84	<5	0.05	<10	<10	29	<10	1152	2
84751	2.3	1.90	666	175	<0.5	<5	5.47	11	19	7	83	4.83	<1	0.35	<10	1.39	2700	<2	0.01	3	1151	34	1.73	<5	3	104	<5	<0.01	<10	<10	42	<10	91	2
84752	2.3	1.14	1663	94	<0.5	<5	10.73	30	21	20	76	5.65	<1	0.33	<10	0.79	3848	<2	0.01	9	1172	33	>5.00	13	4	208	<5	<0.01	<10	12	39	<10	47	2
84753	2.1	1.09	323	95	<0.5	<5	11.25	5	20	20	88	4.85	<1	0.26	<10	0.90	3584	<2	0.01	9	1189	19	4.81	<5	4	213	<5	<0.01	<10	10	43	<10	32	2
84754	2.1	0.79	612	96	<0.5	<5	12.75	11	19	21	68	4.26	<1	0.23	<10	0.60	3529	<2	0.01	9	1070	24	4.51	<5	3	226	<5	<0.01	<10	<10	33	<10	30	1
84755	2.9	0.88	1665	53	<0.5	<5	10.25	30	21	22	80	5.41	<1	0.30	<10	0.61	3156	<2	0.01	10	1297	36	>5.00	10	4	186	<5	<0.01	<10	10	33	<10	54	2
84756	1.3	1.98	585	79	<0.5	<5	9.18	11	24	33	51	5.95	<1	0.26	<10	1.72	2859	<2	0.01	11	1181	79	3.59	<5	6	181	<5	<0.01	<10	<10	87	<10	142	2
84757	2.3	1.90	291	119	<0.5	<5	6.14	15	22	31	108	5.86	<1	0.31	<10	1.53	2139	<2	0.01	9	1138	335	3.80	<5	5	124	<5	<0.01	<10	<10	74	11	1073	2
84758	1.9	1.52	902	56	<0.5	<5	6.95	18	22	54	63	5.71	<1	0.22	<10	1.42	2181	<2	0.01	12	1003	253	4.68	<5	5	135	<5	<0.01	<10	<10	72	<10	346	2
84759	0.9	1.01	204	73	<0.5	<5	10.01	3	16	26	29	4.38	<1	0.22	<10	0.93	2430	2	0.01	7	835	96	3.49	<5	4	192	<5	<0.01	<10	<10	39	<10	70	1
84760	1.1	1.92	505	105	<0.5	<5	7.96	10	24	42	71	5.99	<1	0.23	<10	2.23	2537	<2	0.01	11	1126	82	3.08	<5	7	186	<5	<0.01	<10	<10	82	<10	211	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2699-RA1

Company: **Ascot Resources Ltd**
 Project: **Dilworth/shipment13**
 Attn: **Sue Deane**

Aug-08-08

We hereby certify the following assay of 24 core samples submitted Jul-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %	Zn %
85168	0.11	0.12	1.9		
85169	0.06		0.6		
85170	0.10		1.9		
85171	0.09		1.4		
85172	0.16		1.9		
85173	0.09		1.0		
85174	0.07		1.5		
85175	0.13		0.4		
85175A	6.09		3.5		
85176	0.08	0.08	1.1		
85177	0.20		23.5		
85178	0.14		1.3		
85179	0.19		2.7		
85180	0.36		5.5		
85181	0.50		5.4		1.30
85182	0.59		10.8		1.77
85183	1.04		13.0		1.38
85184	2.45		48.9	2.57	3.19
85185	0.53		20.5		2.63
85186	0.65	0.85	67.0	1.42	3.45
85187	0.32		11.3		1.28
85188	0.15		3.2		
85189	0.15		2.4		
85190	0.34		10.7		1.08
*0218	0.89				
*CCu-1c				0.33	3.92
*BLANK	<0.01			<0.01	<0.01

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2699-RA2

Company: **Ascot Resources Ltd**
 Project: **Dilworth/shipment13**
 Attn: **Sue Deane**

Aug-08-08

We hereby certify the following assay of 24 core samples submitted Jul-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %	Zn %
85191	0.57	0.59	4.0		
85192	0.22		1.3		
85193	0.47		8.8		1.27
85194	0.04		0.7		
85195	0.18		2.1		
85196	0.85		7.8		
85197	1.60		22.5		2.29
85198	1.02		9.2		2.52
85199	1.91		23.0		3.71
85200	<0.01	0.02	<0.1		
85201	5.56		100	4.48	3.91
85202	1.51		15.1	1.27	1.79
85203	5.13		10.1		
85204	1.09		3.4		
85205	0.39		20.5	1.58	
85206	0.87		29.8	1.72	2.18
85207	0.92		35.2	2.25	2.26
85208	0.42		40.4	1.20	1.82
85209	0.85		32.3	1.70	5.20
85210	0.28	0.28	3.4		
85211	0.24		4.9		
85212	0.17		7.2		
*0218	0.95				
*CCu-1c				0.34	3.90
*BLANK	<0.01			<0.01	<0.01

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2699RJ**

Date : Aug-08-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment13

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
85168	1.9	1.19	169	139	<0.5	<5	2.60	9	10	66	20	5.22	<1	0.23	<10	0.98	1777	3	0.01	5	875	659	1.69	5	4	83	<5	<0.01	<10	<10	38	<10	1057	4
85169	0.6	0.89	63	260	<0.5	<5	2.20	3	9	138	19	3.68	<1	0.21	<10	0.81	1557	4	0.01	9	653	103	0.69	5	3	103	<5	<0.01	<10	<10	29	<10	337	3
85170	1.9	1.23	97	98	<0.5	<5	1.90	22	9	97	55	4.43	<1	0.15	<10	0.98	1788	7	0.01	5	612	1393	1.36	<5	3	75	<5	<0.01	<10	<10	41	<10	2870	3
85171	1.4	0.89	117	81	<0.5	<5	2.18	16	9	145	67	4.24	<1	0.19	<10	0.92	1864	6	0.01	7	627	1163	1.35	6	3	97	<5	<0.01	<10	<10	29	<10	2010	3
85172	1.9	0.88	232	71	<0.5	<5	2.07	29	9	115	47	5.59	<1	0.17	<10	0.97	2185	5	<0.01	6	578	858	3.32	5	3	97	<5	<0.01	<10	<10	31	<10	3762	4
85173	1.0	1.24	96	64	<0.5	<5	2.71	11	7	144	37	3.94	<1	0.10	<10	0.96	1836	16	0.01	6	499	817	1.30	5	3	54	5	<0.01	<10	<10	43	<10	1422	3
85174	1.5	1.22	150	87	<0.5	<5	2.27	12	8	97	53	3.75	<1	0.15	<10	0.96	1853	2	0.01	5	648	1313	0.82	<5	3	84	<5	<0.01	<10	<10	45	<10	1461	3
85175	0.4	0.37	162	87	<0.5	<5	5.09	2	8	190	12	4.09	<1	0.24	<10	0.88	2619	4	0.01	7	505	97	1.60	<5	3	340	<5	<0.01	<10	<10	13	<10	193	3
85175A	3.5	2.01	685	134	1.0	220	10.74	3	55	144	558	7.48	13	0.22	19	0.44	1174	139	0.06	85	911	101	2.53	6	5	135	10	0.19	<10	<10	62	39	115	26
85176	1.1	1.23	73	90	<0.5	<5	3.64	1	9	136	34	3.88	<1	0.20	<10	0.79	1910	5	0.01	6	742	17	1.05	<5	4	115	<5	<0.01	<10	<10	46	<10	76	3
85177	23.5	1.41	71	86	<0.5	9	1.96	1	11	173	40	4.14	<1	0.20	<10	0.76	1110	7	0.02	7	772	66	0.85	5	3	73	5	<0.01	<10	<10	63	<10	89	3
85178	1.3	1.86	66	221	<0.5	<5	1.80	4	17	72	78	5.44	<1	0.19	<10	1.02	1773	2	0.01	6	1041	117	0.84	<5	5	52	<5	<0.01	<10	<10	88	<10	425	3
85179	2.7	2.14	183	87	<0.5	<5	1.13	13	15	95	74	6.42	<1	0.15	<10	1.55	2482	3	0.01	6	933	578	2.17	5	5	48	<5	<0.01	<10	<10	86	<10	1622	4
85180	5.5	1.06	358	58	<0.5	<5	1.83	75	9	101	83	5.22	<1	0.13	<10	0.87	2055	2	<0.01	6	484	1175	4.03	9	1	52	<5	<0.01	<10	<10	30	<10	9717	3
85181	5.4	1.96	456	47	<0.5	<5	0.92	121	9	108	213	8.32	1	0.08	<10	1.80	3072	<2	<0.01	6	523	857	>5.00	10	3	33	<5	<0.01	<10	<10	51	<10	>10000	5
85182	10.8	1.63	572	31	<0.5	<5	1.25	178	10	89	385	10.75	1	0.05	<10	1.49	2595	<2	<0.01	6	406	3010	>5.00	15	2	28	<5	<0.01	<10	<10	46	<10	>10000	6
85183	13.0	0.57	514	18	<0.5	<5	11.20	138	5	68	289	6.57	<1	0.03	<10	0.52	3680	<2	<0.01	4	193	3143	>5.00	13	2	178	<5	<0.01	<10	<10	19	<10	>10000	4
85184	48.9	0.21	889	13	<0.5	7	1.81	335	10	122	1186	13.32	1	0.04	<10	0.19	1138	<2	<0.01	8	320	>10000	>5.00	42	<1	77	<5	<0.01	<10	<10	21	<10	>10000	8
85185	20.5	0.54	364	45	<0.5	<5	4.71	272	7	112	366	5.13	3	0.08	<10	0.38	2317	<2	<0.01	7	330	2043	>5.00	19	1	126	<5	<0.01	<10	<10	17	<10	>10000	3
85186	67.0	0.36	1217	16	<0.5	<5	1.98	345	9	122	1690	9.78	1	0.03	<10	0.30	1217	<2	<0.01	8	335	>10000	>5.00	66	<1	42	<5	<0.01	<10	<10	19	<10	>10000	6
85187	11.3	1.75	486	57	<0.5	<5	1.87	131	11	76	212	7.07	<1	0.09	<10	1.35	2563	3	<0.01	6	588	2437	4.96	14	2	57	<5	<0.01	<10	<10	59	<10	>10000	4
85188	3.2	1.29	209	108	<0.5	<5	2.49	22	6	105	55	3.50	<1	0.18	<10	0.94	2254	<2	<0.01	5	472	737	1.28	5	2	101	<5	<0.01	<10	<10	34	<10	2588	3
85189	2.4	1.80	148	44	<0.5	<5	1.91	38	6	81	60	5.24	<1	0.07	<10	1.59	2938	<2	<0.01	4	398	615	2.21	5	2	52	<5	<0.01	<10	<10	42	<10	4425	4
85190	10.7	1.67	280	76	<0.5	<5	1.73	100	6	97	105	6.12	<1	0.13	<10	1.38	2618	<2	<0.01	5	448	6025	4.07	14	2	51	<5	<0.01	<10	<10	40	<10	>10000	5
85191	4.0	1.26	320	95	<0.5	5	3.32	51	6	71	42	5.46	1	0.18	<10	1.22	2786	<2	0.01	2	621	798	3.45	<5	2	109	<5	<0.01	<10	<10	32	69	5388	4
85192	1.3	1.03	228	106	<0.5	<5	2.00	10	7	57	14	5.30	<1	0.21	<10	1.05	2131	<2	0.01	1	734	161	2.80	<5	2	157	<5	<0.01	<10	<10	26	11	782	4
85193	8.8	0.61	371	54	<0.5	5	2.59	129	10	111	194	6.50	<1	0.28	<10	0.70	1981	3	0.01	3	825	3297	>5.00	<5	3	218	<5	<0.01	<10	<10	13	177	>10000	4
85194	0.7	1.00	100	240	<0.5	<5	3.06	2	9	39	17	3.40	<1	0.33	<10	0.67	1960	2	0.01	2	1058	50	1.20	<5	2	182	<5	<0.01	<10	<10	22	<10	152	3
85195	2.1	1.31	168	142	<0.5	<5	2.38	8	11	88	39	5.06	<1	0.30	<10	0.91	2267	4	0.01	3	1077	415	2.10	<5	3	110	<5	<0.01	<10	<10	39	10	754	3
85196	7.8	1.25	927	32	<0.5	9	1.63	78	8	82	65	10.65	<1	0.09	<10	1.44	2744	<2	0.01	1	531	1828	>5.00	<5	2	79	<5	<0.01	<10	<10	31	99	7488	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment13

Sample type:

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2699RJ**

Date : Aug-08-08

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
85197	22.5	1.69	2358	23	<0.5	16	0.35	236	11	89	196	>15.00	<1	0.07	<10	1.44	2296	<2	0.01	<1	863	6604	>5.00	<5	2	12	<5	<0.01	<10	<10	49	337	>10000	8
85198	9.2	0.98	836	29	<0.5	9	2.47	233	12	79	273	9.49	1	0.09	<10	0.98	2481	4	0.01	2	667	1377	>5.00	<5	2	74	<5	<0.01	<10	<10	31	359	>10000	4
85199	23.0	0.47	1193	30	<0.5	10	2.58	341	12	143	686	11.85	1	0.10	<10	0.59	2008	3	0.01	4	549	6219	>5.00	<5	1	94	<5	<0.01	<10	<10	14	496	>10000	5
85200	<0.2	0.86	<5	255	0.7	<5	0.46	2	8	148	3	2.25	<1	0.49	<10	0.59	602	<2	0.06	7	803	34	0.07	<5	2	35	<5	0.12	<10	<10	38	<10	222	2
85201	100.8	0.13	1309	25	<0.5	10	3.11	378	9	119	2247	14.20	<1	0.06	<10	0.43	2143	<2	<0.01	1	512	>10000	>5.00	50	1	157	<5	<0.01	<10	<10	5	517	>10000	6
85202	15.1	0.35	1008	40	<0.5	7	3.11	186	6	118	270	8.02	<1	0.12	<10	0.57	2088	2	0.01	2	444	>10000	>5.00	<5	1	125	<5	<0.01	<10	<10	9	271	>10000	3
85203	10.1	0.33	510	50	<0.5	5	2.72	56	8	199	97	6.08	<1	0.15	<10	0.79	2525	2	0.01	6	445	1435	>5.00	<5	1	129	<5	<0.01	<10	<10	8	71	5640	3
85204	3.4	0.26	323	53	<0.5	<5	9.65	30	7	86	54	3.94	<1	0.12	<10	0.48	3010	3	0.01	4	498	358	3.26	<5	3	237	<5	<0.01	<10	<10	11	40	3064	2
85205	20.5	0.29	447	30	<0.5	7	4.89	91	9	88	604	9.46	<1	0.05	<10	0.37	2491	<2	<0.01	4	364	>10000	>5.00	<5	1	114	<5	<0.01	<10	<10	8	126	9621	4
85206	29.8	0.24	800	38	<0.5	5	3.30	212	11	54	2175	11.64	<1	0.06	<10	0.62	2976	<2	<0.01	2	510	>10000	>5.00	5	1	147	<5	<0.01	<10	<10	8	304	>10000	5
85207	35.2	0.24	869	30	<0.5	7	2.95	220	10	67	2402	12.67	<1	0.04	<10	0.38	2773	<2	<0.01	2	501	>10000	>5.00	14	1	83	<5	<0.01	<10	<10	9	322	>10000	5
85208	40.4	0.12	483	27	<0.5	11	1.67	184	17	170	1139	10.49	<1	0.04	<10	0.32	1270	<2	0.01	4	335	>10000	>5.00	6	<1	58	<5	<0.01	<10	<10	5	278	>10000	4
85209	32.3	0.61	817	21	<0.5	10	1.07	445	14	115	1299	12.67	<1	0.06	<10	0.82	1895	<2	0.01	2	441	>10000	>5.00	<5	1	50	<5	<0.01	<10	<10	18	704	>10000	6
85210	3.4	0.36	264	65	<0.5	<5	2.45	27	9	137	95	5.17	<1	0.14	<10	0.48	1424	5	0.01	5	508	711	4.61	<5	1	95	<5	<0.01	<10	<10	11	37	3002	2
85211	4.9	0.27	429	94	<0.5	<5	2.56	29	10	231	136	5.13	<1	0.22	<10	0.43	1427	13	0.01	7	618	1720	4.76	<5	1	107	<5	<0.01	<10	<10	7	37	2900	2
85212	7.2	0.22	271	70	<0.5	<5	2.92	18	8	135	275	3.90	<1	0.12	<10	0.25	1454	8	0.01	4	438	895	3.38	<5	1	103	<5	<0.01	<10	<10	8	20	1617	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Quality Assaying for over 25 Years

Assay Certificate

8V-2768-RA1

Company: **Ascot resources Ltd**
Project: **Dilworth/shipment 14**
Attn: **Sue Deane**

Aug-27-08

We hereby certify the following assay of 22 core samples submitted Jul-31-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
84866	0.16	0.17	4.5	
84867	0.02		<0.1	
84868	0.06		2.0	
84869	0.27		2.2	
84870	0.08		2.7	
84871	0.05		1.5	
84872	0.06		4.5	
84873	0.28		10.5	
84874	0.55		6.7	
84875	1.83	1.85	190	
84876	0.27		18.2	1.34
84877	0.30		7.0	
84878	0.08		2.8	
84879	0.29		4.2	
84880	0.59		12.6	3.96
84881	0.06		1.9	
84882	0.18		4.8	
84883	0.28		4.6	
84884	0.21		4.3	
84885	0.11	0.14	3.3	
84886	0.05		1.1	
84887	0.12		1.8	
*0218	0.87			
*CCu-1c				3.93
*BLANK	<0.01			<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2768-RA2

Company: **Ascot resources Ltd**
Project: **Dilworth/shipment 14**
Attn: **Sue Deane**

Aug-27-08

We hereby certify the following assay of 22 core samples submitted Jul-31-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84888	0.24	0.24	2.6
84889	0.09		1.0
84890	0.13		0.8
84891	0.13		1.0
84892	0.14		1.1
84893	0.14		1.4
84937	0.13		3.1
84938	0.13		7.3
84939	0.17		3.7
84940	0.12	0.11	5.7
84941	0.09		2.6
84942	0.10		3.0
84943	0.15		12.2
84944	0.22		5.4
84945	0.17		5.4
84946	0.22		4.2
84947	0.10		2.3
84948	0.09		1.2
84949	0.11		1.5
84950	0.01	<0.01	<0.1
84951	0.06		1.9
84952	0.07		2.0
*0218	0.92		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2768-RA3

Company: **Ascot resources Ltd**
Project: **Dilworth/shipment 14**
Attn: **Sue Deane**

Aug-27-08

We hereby certify the following assay of 22 core samples submitted Jul-31-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
84953	0.07	0.08	1.3	
84954	0.07		1.5	
84955	0.06		2.5	
84956	0.05		4.8	
84957	0.12		7.5	
84958	0.12		5.0	
84959	0.14		2.6	
84960	0.20		1.5	
84961	0.12		1.2	
84962	0.12	0.13	2.4	
84963	0.06		0.5	
84964	0.05		0.3	
84965	0.29		0.5	
84966	0.14		<0.1	
84967	0.06		0.1	
84968	0.07		0.3	
84969	<0.01		<0.1	
84970	<0.01		<0.1	
84971	0.47		9.9	
84972	0.57	0.55	8.8	1.10
84973	0.63		8.6	1.03
84974	0.39		1.8	
*0218	0.95			
*CCu-1c				4.00
*BLANK	<0.01			<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2768-RA4

Company: **Ascot resources Ltd**
Project: **Dilworth/shipment 14**
Attn: **Sue Deane**

Aug-27-08

We hereby certify the following assay of 22 core samples submitted Jul-31-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %	Zn %
84975	1.68	1.79	187		
84976	0.56		4.4		
84977	0.53		5.8		
84978	0.21		3.1		
84979	0.52		3.5		
84980	0.38		2.7		
84981	0.63		5.4		
84982	0.34		4.3		
84983	0.30		3.4		
84984	0.23	0.23	2.3		
84985	0.09		1.4		
84986	0.21		2.9		
84987	0.54		6.6		1.01
84988	0.08		1.8		
84989	0.15		3.1		
84990	0.37		5.6		
84991	0.16		17.9	0.99	2.03
84992	0.41		3.6		
84993	0.09		4.3		
84994	0.15	0.15	4.9		
84995	0.36		2.9		
84996	0.11		2.5		
*0218	0.92				
*CCu-1c				0.33	3.93
*BLANK	<0.01			<0.01	<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2768-RA5

Company: **Ascot resources Ltd**
Project: **Dilworth/shipment 14**
Attn: **Sue Deane**

Aug-27-08

We hereby certify the following assay of 22 core samples submitted Jul-31-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
84997	0.06	0.05	1.9
84998	0.10		2.6
84999	0.14		3.1
85000	<0.01		<0.1
85001	0.14		4.3
85002	0.14		1.3
85003	0.31		2.2
85004	0.04		0.2
85005	0.11		1.9
85006	0.03	<0.01	0.2
85007	0.14		3.3
85008	0.57		3.2
85009	0.06		2.5
85010	0.02		0.2
85011	0.04		2.2
85012	0.03		2.0
85013	0.04		0.5
85014	0.10		2.7
85015	0.16		6.0
85016	0.16	0.16	4.4
85017	0.09		5.3
85018	0.13		2.5
*0218	0.92		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2768-RA6

Company: **Ascot resources Ltd**
Project: **Dilworth/shipment 14**
Attn: **Sue Deane**

Aug-27-08

We hereby certify the following assay of 22 core samples submitted Jul-31-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
85019	0.03	0.03	1.3	
85020	0.15		3.2	
85021	<0.01		<0.1	
85022	0.05		1.7	
85023	0.03		0.7	
85024	<0.01		<0.1	
85025	1.35		>200	219.2
85026	<0.01		<0.1	
85027	0.31		4.7	
85028	0.12	0.14	2.6	
85029	0.09		2.1	
85030	0.07		2.1	
85031	0.27		0.5	
85032	0.29		1.3	
85033	0.30		1.2	
85034	0.04		<0.1	
85035	0.07		0.3	
85036	0.12		<0.1	
85037	0.23		1.9	
85038	0.08	0.08	0.5	
85039	0.01		<0.1	
85040	0.46		8.2	
*0218	0.95			
*CCu-1c				129.3
*BLANK	<0.01			<0.1

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2768-RA7

Company: **Ascot resources Ltd**
Project: **Dilworth/shipment 14**
Attn: **Sue Deane**

Aug-27-08

We hereby certify the following assay of 22 core samples
submitted Jul-31-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %	Zn %
85041	0.23	0.24	0.6		
85042	0.12		1.6		
85043	0.26		1.4		
85044	0.11		3.1		
85045	<0.01		<0.1		
85046	0.80		7.1		1.19
85047	0.27		4.1		
85048	0.30		2.5		
85049	0.92		3.6		
85050	<0.01	<0.01	<0.1		
85051	0.31		1.8		
85052	0.32		2.7		
85053	0.23		2.5		
85054	0.20		3.7		
85055	0.23		2.5		
85056	0.46		27.1	1.45	
85057	0.84		3.8		
85058	0.26		2.3		
85059	0.13		0.7		
85060	2.40	2.57	27.4	2.99	2.08
85061	0.15		2.4		
85062	0.15		1.8		
*0218	0.90				
*CCu-1c				0.33	3.93
*BLANK	<0.01			<0.01	<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2768-RA8

Company: **Ascot resources Ltd**
Project: **Dilworth/shipment 14**
Attn: **Sue Deane**

Aug-27-08

We hereby certify the following assay of 24 core samples submitted Jul-31-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %	Zn %
85063	0.26	0.26	2.9		
85064	0.25		2.8		
85065	0.15		3.0		
85066	0.30		8.5		
85067	0.18		4.6		
85068	0.61		79.9	5.80	2.23
85069	0.27		5.4		
85070	0.11		3.2		
85071	0.07		3.5		
85072	0.21	0.22	4.5		
85073	0.31		3.3		
85074	0.11		6.3		
85075	6.34		2.9		
85076	0.12		4.1		
85077	0.22		3.0		
85078	0.12		2.6		
85079	0.31		9.5		
85080	0.09		3.1		
85081	0.02		0.2		
85082	0.01	0.02	<0.1		
85083	0.03		<0.1		
85084	0.03		0.9		
*0218	0.96				
*CCu-1c				0.33	4.00
*BLANK	<0.01			<0.01	<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2768-RA9

Company: **Ascot resources Ltd**
Project: **Dilworth/shipment 14**
Attn: **Sue Deane**

Aug-27-08

We hereby certify the following assay of 22 core samples submitted Jul-31-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
85085	0.11	0.11	3.6
85086	0.12		3.4
85087	0.28		5.8
85088	0.08		4.4
85089	0.09		3.8
85090	0.09		5.8
85091	0.09		6.2
85092	0.08		11.0
85093	0.14		12.7
85094	0.20	0.26	4.6
85095	0.10		8.7
85096	0.16		11.3
85097	0.21		24.5
85098	0.12		7.1
85099	0.36		5.6
85100	<0.01		<0.1
85101	0.17		3.8
85102	0.23		2.5
85103	0.13		1.1
85104	0.12	0.15	1.2
85105	0.17		1.1
85106	<0.01		<0.1
*0218	0.94		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2768-RA10

Company: **Ascot resources Ltd**
Project: **Dilworth/shipment 14**
Attn: **Sue Deane**

Aug-27-08

We hereby certify the following assay of 22 core samples submitted Jul-31-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
85107	0.01	0.01	0.4	
85108	0.40		1.9	
85109	0.16		2.5	
85110	0.30		4.0	
85111	0.22		2.9	
85112	0.10		3.6	
85113	0.20		4.5	
85114	0.11		1.3	
85115	0.01		<0.1	
85116	0.05	0.06	1.5	
85117	0.10		1.9	
85118	0.06		1.4	
85119	0.07		1.1	
85120	0.09		2.1	
85121	0.10		2.7	
85122	0.03		3.9	
85123	0.19		7.7	1.76
85124	0.16		5.4	
85125	0.49		2.0	
85126	0.24	0.25	2.3	
85127	0.50		1.7	
85128	0.56		4.4	
*0218	0.93			
*CCu-1c				4.00
*BLANK	<0.01			<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2768-RA11

Company: **Ascot resources Ltd**
Project: **Dilworth/shipment 14**
Attn: **Sue Deane**

Aug-27-08

We hereby certify the following assay of 22 core samples submitted Jul-31-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
85129	1.18	1.10	8.1	
85130	0.16		3.0	
85131	0.20		2.2	
85132	0.46		5.0	
85133	0.28		5.3	
85134	0.29		11.2	
85135	0.03		4.1	
85136	0.13		3.5	
85137	0.12		4.2	
85138	0.19	0.21	1.6	
85139	0.21		2.9	
85140	0.12		2.4	
85141	0.75		2.6	
85142	0.49		2.7	
85153	0.02		<0.1	
85154	0.08		0.1	
85155	0.05		0.1	
85156	0.05		0.2	
85157	1.03		0.5	
85158	0.20	0.21	1.1	
85159	1.47		12.6	1.92
85160	0.96		7.9	1.87
*0218	0.91			
*CCu-1c				4.00
*BLANK	<0.01			<0.01

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2768-RA12

Company: **Ascot resources Ltd**
 Project: **Dilworth/shipment 14**
 Attn: **Sue Deane**

Aug-27-08

We hereby certify the following assay of 22 core samples submitted Jul-31-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne	Pb %	Zn %
85161	0.08	0.08	0.6			
85162	0.10		0.2			
85163	0.10		1.0			
85164	0.17		9.9		1.01	0.98
85165	0.12		3.6			
85166	0.06		1.7			
85167	0.10		0.9			
85213	0.20		3.3			
85214	0.13		1.6			
85215	0.12	0.11	3.0			
85216	0.10		2.0			
85217	0.08		2.0			
85218	0.17		2.4			
85219	0.15		2.9			
85220	0.04		1.5			
85221	0.06		1.8			
85222	0.06		1.0			
85223	0.12		0.5			
85224	0.37		6.8			
85225	1.31	1.36	>200	209.3		
85226	0.52		3.8			
85227	0.12		2.8			
*0218	0.96					
*CCu-1c				131.3	0.35	3.93
*BLANK	<0.01			<0.1	<0.01	<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2768-RA13

Company: **Ascot resources Ltd**
Project: **Dilworth/shipment 14**
Attn: **Sue Deane**

Aug-27-08

We hereby certify the following assay of 22 core samples submitted Jul-31-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
85228	0.02	0.03	1.0
85229	0.74		2.6
85230	0.01		<0.1
85231	<0.01		<0.1
139218	0.05		5.2
139219	0.02		1.8
139220	0.40		2.4
139221	0.30		2.6
139222	0.05		0.7
139223	1.51	1.38	3.4
139224	0.23		2.1
139225	0.14		2.0
139226	0.16		1.4
139227	0.19		1.8
139228	0.16		1.8
139229	0.08		0.5
139230	0.64		3.6
139231	0.16		2.4
139232	0.06		<0.1
139233	0.04	0.03	<0.1
139234	0.03		<0.1
139235	0.02		<0.1
*0218	0.92		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2768-RA14

Company: **Ascot resources Ltd**
Project: **Dilworth/shipment 14**
Attn: **Sue Deane**

Aug-27-08

We hereby certify the following assay of 22 core samples submitted Jul-31-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
139236	0.04	0.05	<0.1
139237	0.07		<0.1
139238	0.04		<0.1
139239	0.04		<0.1
139240	0.02		0.2
139241	0.46		0.9
139242	0.12		4.9
139243	0.03		<0.1
139244	0.06		0.3
139245	0.01	0.02	<0.1
139246	<0.01		<0.1
139247	<0.01		<0.1
139248	<0.01		<0.1
139249	0.01		<0.1
139250	<0.01		0.3
139251	0.02		0.5
139252	0.02		0.6
139253	0.01		1.7
139254	<0.01		1.6
139255	<0.01	0.01	0.4
139268	0.71		35.9
139269	0.80		47.0
*0218	0.92		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-2768-RA15

Company: **Ascot resources Ltd**
Project: **Dilworth/shipment 14**
Attn: **Sue Deane**

Aug-27-08

We hereby certify the following assay of 22 core samples submitted Jul-31-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
139270	0.88	0.80	57.2	
139271	0.52		25.1	
139272	0.64		8.8	
139273	5.27		>200	712.5
139274	0.97		49.7	
139275	0.59		24.0	
139276	0.76		11.5	
139277	0.77		40.0	
139278	1.53		18.7	
139279	0.12	0.12	7.0	
139280	0.38		37.8	
85143	0.69		12.7	
85144	0.87		2.5	
85145	0.60		2.9	
85146	0.72		2.9	
85147	0.50		2.4	
85148	0.35		1.8	
85149	0.33		2.0	
85150	0.32		1.9	
85151	0.02	<0.01	<0.1	
85152	0.53		2.1	
*0218	0.91			
*CCu-1c				131.6
*BLANK	<0.01			<0.1

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2768RJ

Date : Aug-27-08

Ascot resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 14

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84866	4.5	1.26	200	95	<0.5	<5	2.20	12	12	85	141	6.00	<1	0.27	<10	0.75	1856	9	0.01	4	823	1808	>5.00	<5	3	55	<5	<0.01	<10	<10	44	12	1381	3
84867	<0.2	1.21	<5	859	0.5	14	2.42	<1	9	79	6	2.31	<1	0.42	21	0.67	610	2	0.05	6	812	60	0.37	<5	3	111	<5	0.01	<10	<10	33	27	94	7
84868	2.0	0.57	78	169	<0.5	<5	5.40	9	12	113	111	4.07	<1	0.33	<10	0.60	1644	6	0.01	3	765	156	2.27	<5	3	171	<5	<0.01	<10	<10	13	<10	1035	2
84869	2.2	0.76	182	125	<0.5	9	2.28	14	13	162	57	5.53	<1	0.34	<10	0.74	1764	7	0.01	6	797	352	3.90	<5	3	128	<5	<0.01	<10	<10	31	24	1347	3
84870	2.7	0.98	172	134	<0.5	<5	3.49	9	11	77	105	4.38	<1	0.24	<10	0.69	2346	13	0.01	3	822	331	2.60	<5	3	96	<5	<0.01	<10	<10	52	<10	719	2
84871	1.5	1.36	131	141	<0.5	5	2.11	4	11	146	77	4.13	<1	0.28	<10	0.80	2096	8	0.01	4	877	77	1.63	<5	4	51	<5	<0.01	<10	<10	58	11	311	2
84872	4.5	1.39	137	108	<0.5	<5	5.42	10	12	75	242	4.42	<1	0.25	<10	0.77	2731	8	0.01	3	914	613	2.09	<5	4	79	<5	<0.01	<10	<10	59	<10	1040	2
84873	10.5	1.21	518	60	<0.5	6	0.96	36	17	188	362	7.40	<1	0.26	<10	0.78	1837	19	0.01	6	951	2196	>5.00	5	3	24	<5	<0.01	<10	<10	57	34	3522	3
84874	6.7	1.19	707	60	<0.5	5	2.63	49	15	88	145	8.20	<1	0.15	<10	0.85	2285	11	0.01	3	731	1215	>5.00	<5	3	41	<5	<0.01	<10	<10	50	34	4383	3
84875	190.2	0.99	212	239	0.5	90	6.12	6	19	26	3787	4.06	4	0.18	<10	0.21	759	64	0.03	37	677	250	1.60	216	2	200	<5	0.07	<10	<10	26	17	285	11
84876	18.2	0.62	404	62	<0.5	5	3.94	122	10	185	890	6.72	<1	0.18	<10	0.39	2169	56	0.01	5	539	7532	>5.00	8	1	62	<5	<0.01	<10	<10	26	127	>10000	3
84877	7.0	1.49	567	55	<0.5	<5	4.38	66	14	66	129	9.66	<1	0.19	<10	1.07	3087	9	0.01	2	849	2787	>5.00	<5	3	75	<5	0.02	<10	10	59	51	6416	4
84878	2.8	1.93	178	75	<0.5	<5	7.94	5	25	215	148	5.49	<1	0.15	<10	1.33	3630	28	0.01	21	1265	227	1.96	<5	14	141	<5	0.06	<10	<10	134	<10	375	3
84879	4.2	1.64	119	69	0.7	<5	3.79	32	29	196	316	5.43	<1	0.20	<10	1.11	2578	32	0.01	24	1250	422	2.78	<5	12	55	<5	0.10	<10	<10	114	31	3694	3
84880	12.6	1.24	396	36	<0.5	9	5.14	337	20	108	404	11.18	1	0.04	<10	0.93	2965	15	0.01	14	643	7339	>5.00	<5	7	87	<5	0.02	<10	10	67	340	>10000	5
84881	1.9	2.68	53	87	1.1	<5	10.74	4	29	230	91	6.18	<1	0.16	<10	1.99	3880	20	0.01	33	1546	36	0.83	<5	20	223	<5	0.11	<10	<10	164	<10	554	7
84882	4.8	2.32	120	83	0.8	<5	11.62	6	25	225	225	7.49	<1	0.10	<10	1.57	3903	30	0.01	27	1251	265	3.33	<5	20	246	<5	0.08	<10	<10	158	10	621	6
84883	4.6	2.91	53	81	0.7	<5	11.06	1	27	252	308	8.26	<1	0.12	<10	1.88	3679	20	0.01	30	1471	70	1.78	<5	26	394	<5	0.06	<10	<10	190	<10	216	4
84884	4.3	3.68	75	39	0.9	<5	11.83	2	30	211	220	9.86	<1	0.08	<10	2.54	4447	52	0.01	33	1221	45	2.40	<5	22	276	<5	0.11	<10	10	180	<10	286	6
84885	3.3	1.82	54	132	0.6	<5	5.58	3	18	113	325	4.74	<1	0.27	<10	1.18	2345	23	0.02	8	983	138	1.44	<5	11	88	<5	0.09	<10	<10	109	<10	338	3
84886	1.1	1.38	44	157	<0.5	<5	4.65	1	18	84	136	4.06	<1	0.27	<10	0.91	1744	23	0.02	7	723	135	1.50	<5	5	102	<5	0.01	<10	<10	51	<10	98	3
84887	1.8	1.98	89	145	<0.5	<5	9.99	2	26	197	223	5.52	<1	0.26	<10	1.42	3268	25	0.03	26	1185	34	0.67	<5	17	247	<5	0.04	<10	<10	144	<10	164	4
84888	2.6	1.95	71	96	<0.5	<5	8.42	2	20	127	271	4.86	<1	0.19	<10	1.14	2780	27	0.01	16	1178	23	0.67	<5	13	225	<5	<0.01	<10	<10	105	<10	181	2
84889	1.0	1.59	55	201	<0.5	<5	5.13	1	12	69	117	4.09	<1	0.18	<10	0.89	2086	23	0.02	4	894	14	0.54	<5	7	144	<5	<0.01	<10	<10	78	<10	122	2
84890	0.8	1.75	76	89	<0.5	<5	4.17	1	12	59	60	4.64	<1	0.20	<10	1.04	2123	21	0.02	3	930	24	0.83	<5	6	138	<5	<0.01	<10	<10	68	<10	127	2
84891	1.0	1.71	69	126	<0.5	<5	3.45	2	12	69	101	4.33	<1	0.22	10	0.96	1980	14	0.01	4	996	72	0.52	<5	6	151	<5	<0.01	<10	<10	72	<10	196	2
84892	1.1	1.65	60	116	0.5	<5	3.83	3	14	55	91	4.35	<1	0.28	<10	0.83	1737	19	0.02	3	984	30	0.80	<5	5	97	<5	0.04	<10	<10	62	<10	249	2
84893	1.4	1.55	80	113	<0.5	<5	6.02	3	12	62	101	3.99	<1	0.27	<10	0.77	2530	258	0.02	2	858	19	0.69	<5	5	99	<5	0.04	<10	<10	63	<10	203	2
84937	3.1	0.30	108	69	<0.5	<5	4.45	8	5	135	33	2.36	<1	0.15	<10	0.17	1570	4	0.01	3	279	645	2.03	<5	1	135	<5	<0.01	<10	<10	8	<10	870	1
84938	7.3	0.43	165	114	<0.5	<5	3.39	30	10	107	170	4.44	<1	0.22	<10	0.58	2246	10	0.01	2	739	3807	3.70	6	3	191	<5	<0.01	<10	<10	18	24	3129	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2768RJ**

Date : Aug-27-08

Ascot resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 14

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84939	3.7	0.37	184	85	<0.5	<5	8.50	11	8	79	91	4.01	<1	0.16	<10	0.38	3584	4	0.01	2	613	548	4.00	<5	2	349	<5	<0.01	<10	<10	13	<10	906	2
84940	5.7	0.49	185	104	<0.5	<5	5.47	18	9	103	91	4.11	<1	0.20	<10	0.46	2459	7	0.01	2	721	1837	3.81	<5	2	227	<5	<0.01	<10	<10	17	15	1862	2
84941	2.6	0.91	141	230	<0.5	<5	2.73	10	8	105	79	4.03	<1	0.26	<10	0.81	2309	2	0.01	2	858	572	1.96	<5	4	159	<5	<0.01	<10	<10	29	<10	1022	2
84942	3.0	0.70	123	142	<0.5	<5	3.10	14	9	113	97	3.93	<1	0.27	<10	0.59	2155	27	0.01	2	811	699	2.54	<5	3	150	<5	<0.01	<10	<10	21	12	1576	2
84943	12.2	0.53	463	72	<0.5	<5	4.60	78	8	106	590	5.88	<1	0.15	<10	0.34	2101	5	0.01	2	660	7627	>5.00	<5	2	131	<5	<0.01	<10	<10	28	73	9106	2
84944	5.4	0.58	276	93	<0.5	<5	5.30	20	12	93	268	4.78	<1	0.16	<10	0.42	2501	28	0.01	3	725	1534	4.61	<5	3	177	<5	<0.01	<10	<10	45	16	2023	2
84945	5.4	0.84	296	120	<0.5	<5	5.82	29	13	79	316	4.76	<1	0.15	<10	0.58	2815	36	0.01	4	862	1253	4.18	<5	3	165	<5	<0.01	<10	<10	63	24	3081	2
84946	4.2	0.52	212	72	<0.5	<5	11.90	19	8	81	177	3.15	<1	0.09	<10	0.37	3498	44	0.01	3	384	764	2.55	<5	3	286	<5	<0.01	<10	<10	36	14	1806	1
84947	2.3	1.07	148	114	<0.5	<5	4.15	6	11	108	160	4.07	<1	0.17	<10	0.78	2690	29	0.01	4	736	309	2.00	<5	4	148	<5	<0.01	<10	<10	60	<10	521	2
84948	1.2	1.28	117	156	<0.5	<5	4.72	3	9	74	66	3.59	<1	0.22	<10	0.79	2399	7	0.01	2	773	76	1.10	<5	3	193	<5	<0.01	<10	<10	48	<10	184	2
84949	1.5	0.82	210	108	<0.5	<5	5.18	5	7	110	26	2.82	<1	0.13	<10	0.61	2399	62	0.01	2	582	162	1.49	<5	3	143	<5	<0.01	<10	<10	44	<10	242	1
84950	<0.2	1.17	<5	288	0.9	<5	0.69	<1	10	193	<1	2.44	<1	0.54	13	0.65	704	2	0.09	6	801	8	0.01	<5	3	70	5	0.16	<10	<10	46	<10	61	2
84951	1.9	0.90	287	137	<0.5	<5	5.85	8	8	104	76	3.29	<1	0.16	<10	0.56	2713	4	0.01	3	717	137	1.73	<5	3	190	<5	<0.01	<10	<10	48	<10	304	1
84952	2.0	1.12	208	86	<0.5	<5	8.28	6	9	86	64	3.27	<1	0.20	<10	0.66	2785	8	0.01	2	684	157	1.37	<5	3	232	<5	<0.01	<10	<10	40	<10	298	2
84953	1.3	0.84	229	92	<0.5	<5	5.59	6	8	74	73	3.53	<1	0.11	<10	0.61	2198	6	0.01	2	612	245	2.26	<5	3	175	<5	<0.01	<10	<10	45	<10	260	1
84954	1.5	0.95	180	81	<0.5	<5	7.67	6	9	70	97	3.24	<1	0.12	<10	0.63	3133	11	0.01	3	661	154	1.40	<5	4	235	<5	<0.01	<10	<10	49	<10	331	1
84955	2.5	1.09	207	90	<0.5	<5	6.05	11	9	62	204	3.48	<1	0.13	<10	0.75	2907	10	0.01	2	716	458	1.48	<5	4	175	<5	<0.01	<10	<10	53	<10	843	2
84956	4.8	0.82	129	84	<0.5	<5	7.15	35	8	77	83	2.84	<1	0.12	<10	0.62	2964	15	0.01	2	625	2965	1.71	<5	3	175	<5	<0.01	<10	<10	36	34	4420	1
84957	7.5	0.46	255	58	<0.5	<5	5.56	60	6	92	232	2.94	<1	0.08	<10	0.37	2193	4	0.01	2	397	4400	2.79	<5	2	149	<5	<0.01	<10	<10	22	55	7388	1
84958	5.0	0.52	578	75	<0.5	<5	7.70	26	6	80	49	3.07	<1	0.08	<10	0.43	2620	5	0.01	2	417	1669	2.56	<5	2	163	<5	<0.01	<10	<10	27	14	1955	1
84959	2.6	0.61	487	65	<0.5	<5	12.20	15	6	54	72	2.96	<1	0.07	<10	0.48	3684	15	0.01	1	415	434	2.05	<5	2	249	<5	<0.01	<10	<10	30	<10	648	1
84960	1.5	1.20	179	80	<0.5	<5	3.70	7	11	77	69	4.40	<1	0.16	<10	0.85	2250	6	0.01	3	751	260	1.69	<5	3	106	<5	0.01	<10	<10	43	<10	477	2
84961	1.2	1.02	120	76	<0.5	<5	5.32	8	9	57	67	4.02	<1	0.13	<10	0.82	2404	14	0.01	1	676	327	1.99	<5	3	166	<5	<0.01	<10	<10	41	<10	810	2
84962	2.4	0.50	104	73	<0.5	<5	5.37	18	9	83	100	4.32	<1	0.16	<10	0.70	2241	16	0.01	2	683	1301	1.98	<5	3	212	<5	<0.01	<10	<10	18	14	1900	2
84963	0.5	1.40	26	102	<0.5	<5	2.46	1	11	66	57	4.08	<1	0.19	<10	0.93	1703	7	0.02	1	872	313	0.74	<5	4	92	<5	<0.01	<10	<10	47	<10	159	2
84964	0.3	1.46	41	97	<0.5	<5	2.84	1	11	68	54	4.18	<1	0.22	<10	0.84	1712	10	0.01	1	971	17	0.65	<5	4	115	<5	0.01	<10	<10	51	<10	150	2
84965	0.5	1.32	28	88	<0.5	<5	3.45	1	10	61	59	3.91	<1	0.21	<10	0.77	1583	8	0.02	1	914	14	0.70	<5	4	125	<5	<0.01	<10	<10	46	<10	112	2
84966	<0.2	1.37	17	97	<0.5	<5	2.77	<1	10	69	35	3.84	<1	0.22	<10	0.81	1441	7	0.02	2	872	11	0.48	<5	4	101	<5	<0.01	<10	<10	48	<10	108	2
84967	<0.2	1.07	40	89	<0.5	<5	2.89	1	9	92	38	3.54	<1	0.21	<10	0.75	1473	5	0.01	2	810	22	0.71	<5	3	99	<5	<0.01	<10	<10	36	<10	124	2
84968	0.3	1.07	26	78	<0.5	<5	2.93	1	9	83	53	3.58	<1	0.22	<10	0.73	1424	21	0.01	2	808	102	0.68	<5	3	111	<5	<0.01	<10	<10	34	<10	189	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2768RJ**

Date : Aug-27-08

Ascot resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 14

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84969	<0.2	0.95	<5	567	<0.5	<5	2.47	<1	11	56	<1	2.11	<1	0.26	17	0.63	616	<2	0.04	5	750	6	0.35	<5	3	84	<5	<0.01	<10	<10	25	<10	57	5
84970	<0.2	0.89	<5	846	<0.5	<5	1.52	<1	9	49	<1	2.19	<1	0.25	17	0.60	581	<2	0.03	5	763	8	0.25	<5	3	76	<5	<0.01	<10	<10	24	<10	90	6
84971	9.9	1.33	257	80	<0.5	5	0.68	53	14	65	123	6.49	<1	0.22	<10	0.76	1024	2	0.01	1	841	1211	4.33	<5	3	17	<5	<0.01	<10	<10	45	45	6139	3
84972	8.8	0.91	389	49	<0.5	<5	3.78	106	11	66	205	6.71	<1	0.14	<10	0.74	1768	2	0.01	1	637	1867	>5.00	<5	3	131	<5	<0.01	<10	<10	28	88	>10000	3
84973	8.6	1.08	538	56	<0.5	5	2.02	103	14	53	260	7.28	<1	0.15	<10	0.99	2112	8	0.01	1	805	2124	>5.00	<5	4	94	<5	<0.01	<10	<10	43	84	>10000	3
84974	1.8	1.57	254	64	<0.5	<5	1.11	21	16	68	53	6.43	<1	0.15	<10	1.29	2034	9	0.01	2	836	400	3.00	<5	4	42	<5	<0.01	<10	<10	66	16	2090	2
84975	187.8	1.68	182	264	0.7	89	6.67	5	20	210	4169	4.48	4	0.46	11	0.28	895	68	0.07	40	679	269	1.64	212	3	235	<5	0.09	<10	<10	34	13	274	12
84976	4.4	1.97	164	99	<0.5	<5	1.71	28	16	63	107	6.25	<1	0.23	<10	1.33	2430	9	0.01	3	1066	1138	2.51	<5	6	61	<5	<0.01	<10	<10	98	25	3096	3
84977	5.8	1.81	268	97	<0.5	<5	3.48	38	16	108	113	6.74	<1	0.23	<10	1.11	2745	21	0.01	3	962	2242	4.02	<5	5	103	<5	<0.01	<10	<10	80	35	4152	3
84978	3.1	1.60	190	122	<0.5	<5	1.33	22	16	72	104	5.87	<1	0.26	<10	0.96	2035	16	0.01	2	1072	1175	2.77	<5	4	56	<5	<0.01	<10	<10	68	21	2584	3
84979	3.5	2.34	583	88	<0.5	5	0.80	33	18	111	115	9.66	<1	0.24	<10	1.55	2217	4	0.01	3	1103	292	>5.00	<5	6	27	<5	0.01	<10	<10	90	23	2745	4
84980	2.7	2.32	407	73	<0.5	<5	1.32	29	12	67	80	8.35	<1	0.14	<10	1.76	2580	3	0.01	1	922	621	4.98	<5	5	31	<5	<0.01	<10	<10	83	26	3268	3
84981	5.4	1.95	575	74	<0.5	5	1.09	32	16	128	128	9.67	<1	0.16	<10	1.29	2819	21	0.01	3	953	854	>5.00	<5	5	30	<5	<0.01	<10	10	81	26	3140	4
84982	4.3	1.85	248	93	<0.5	<5	1.73	21	15	61	92	7.02	<1	0.19	<10	1.41	2349	10	0.01	2	1073	924	3.59	<5	5	80	<5	<0.01	<10	<10	75	20	2404	3
84983	3.4	1.96	259	103	<0.5	<5	1.11	31	13	125	86	6.91	<1	0.21	<10	1.34	2168	14	0.01	3	1001	1775	3.50	<5	4	51	<5	<0.01	<10	<10	71	29	3633	3
84984	2.3	1.86	202	98	<0.5	<5	1.47	35	11	79	43	6.57	<1	0.20	<10	1.23	1934	4	0.01	2	896	1013	3.10	<5	4	66	<5	<0.01	<10	<10	56	37	4685	3
84985	1.4	1.71	116	115	<0.5	<5	1.35	11	10	165	23	5.26	<1	0.20	<10	1.11	1757	4	0.02	4	821	916	1.80	<5	4	55	<5	<0.01	<10	<10	56	13	1341	2
84986	2.9	1.91	286	87	<0.5	<5	0.96	32	10	74	48	6.83	<1	0.18	<10	1.38	2131	5	0.01	2	814	1143	3.83	<5	4	47	<5	<0.01	<10	<10	51	29	3720	3
84987	6.6	2.36	692	47	<0.5	6	0.89	99	15	89	197	10.66	<1	0.21	<10	1.79	2867	3	0.01	2	1096	1108	>5.00	<5	4	33	<5	<0.01	<10	10	79	90	>10000	4
84988	1.8	0.64	71	141	<0.5	<5	1.48	4	16	45	107	5.20	<1	0.42	<10	0.96	2054	7	0.01	2	1342	49	1.53	<5	4	121	<5	<0.01	<10	<10	21	<10	434	2
84989	3.1	1.39	203	154	<0.5	<5	1.40	8	17	114	123	5.18	<1	0.39	<10	0.99	2235	11	0.01	4	1147	686	1.85	<5	4	73	<5	<0.01	<10	<10	49	<10	782	2
84990	5.6	1.20	500	87	<0.5	<5	1.13	39	15	93	140	6.96	<1	0.31	<10	1.03	2653	5	0.01	3	1103	3355	>5.00	<5	3	69	<5	<0.01	<10	<10	42	32	3981	3
84991	17.9	0.94	631	38	<0.5	6	2.34	180	10	159	379	9.31	<1	0.16	<10	0.89	2586	2	0.01	4	653	>10000	>5.00	<5	2	76	<5	<0.01	<10	<10	30	193	>10000	4
84992	3.6	0.67	285	147	<0.5	<5	1.62	10	12	109	89	5.15	<1	0.26	<10	0.70	2746	8	0.01	4	919	419	2.58	<5	3	84	<5	<0.01	<10	<10	34	<10	895	2
84993	4.3	0.91	204	127	<0.5	<5	3.17	6	12	147	98	4.21	<1	0.32	<10	0.72	2953	9	0.01	6	910	200	2.43	<5	3	141	<5	<0.01	<10	<10	38	<10	393	2
84994	4.9	0.52	320	137	<0.5	<5	4.70	21	10	75	243	3.94	<1	0.24	<10	0.56	2933	7	0.01	4	817	1294	2.74	<5	2	188	<5	<0.01	<10	<10	23	19	2424	2
84995	2.9	1.47	388	131	<0.5	<5	2.55	9	13	104	167	4.56	<1	0.27	<10	0.80	2492	5	0.01	6	858	129	2.00	<5	3	84	<5	<0.01	<10	<10	50	<10	270	2
84996	2.5	1.37	212	162	<0.5	<5	2.32	5	13	60	135	4.36	<1	0.25	<10	0.69	2082	12	0.01	6	917	85	1.62	<5	3	65	<5	<0.01	<10	<10	50	<10	242	2
84997	1.9	1.31	63	96	<0.5	<5	1.70	2	12	49	141	3.62	<1	0.20	<10	0.64	1741	2	0.01	4	875	25	0.87	<5	2	45	<5	<0.01	<10	<10	46	<10	218	2
84998	2.6	1.33	69	91	<0.5	<5	3.00	2	10	49	195	3.58	<1	0.21	<10	0.70	2250	6	0.01	3	826	81	0.98	<5	2	125	<5	<0.01	<10	<10	43	<10	175	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2768RJ

Date : Aug-27-08

Ascot resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 14

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
84999	3.1	1.26	117	101	<0.5	<5	2.83	2	10	52	158	3.58	<1	0.19	<10	0.67	2201	7	0.01	3	781	42	1.05	<5	2	95	<5	<0.01	<10	<10	45	<10	139	2
85000	<0.2	0.99	<5	261	0.8	<5	0.47	<1	9	123	<1	2.08	<1	0.51	<10	0.58	604	<2	0.07	5	750	6	0.01	<5	2	52	5	0.13	<10	<10	41	<10	48	2
85001	4.3	0.72	110	94	<0.5	<5	3.39	4	6	47	131	2.77	<1	0.24	<10	0.33	1837	45	0.01	1	842	203	1.34	<5	2	117	<5	<0.01	<10	<10	20	<10	310	1
85002	1.3	1.13	88	174	<0.5	<5	0.72	3	9	38	118	3.87	<1	0.25	11	0.42	1465	5	0.01	1	1041	23	1.29	<5	2	17	<5	<0.01	<10	<10	43	<10	293	2
85003	2.2	0.77	189	164	<0.5	<5	4.53	8	8	57	71	4.32	<1	0.22	<10	0.30	2581	16	0.01	2	865	74	2.59	<5	2	154	<5	<0.01	<10	<10	27	<10	505	2
85004	0.2	1.26	16	149	<0.5	<5	2.79	1	7	40	4	3.04	<1	0.26	10	0.64	1674	<2	0.01	1	876	8	0.37	<5	2	141	<5	<0.01	<10	<10	41	<10	109	3
85005	1.9	1.18	70	156	<0.5	<5	3.17	22	7	52	58	3.18	<1	0.25	<10	0.68	1744	<2	0.01	1	824	836	1.04	<5	3	142	<5	<0.01	<10	<10	48	16	2004	2
85006	0.2	1.19	19	94	<0.5	<5	3.16	<1	8	43	11	2.88	<1	0.24	10	0.69	1557	<2	0.01	1	839	20	0.60	<5	3	108	<5	<0.01	<10	<10	49	<10	84	2
85007	3.3	1.22	89	168	<0.5	<5	2.13	3	11	97	119	3.45	<1	0.39	<10	0.94	1286	8	0.02	39	868	156	1.74	<5	3	84	<5	0.01	<10	<10	45	<10	257	3
85008	3.2	1.38	88	101	<0.5	<5	2.61	34	10	34	143	4.18	<1	0.18	<10	0.84	2293	12	0.01	1	776	1751	2.12	<5	2	78	<5	0.03	<10	<10	42	23	2880	2
85009	2.5	0.91	48	109	<0.5	<5	4.23	3	8	24	126	2.35	<1	0.19	<10	0.44	2596	15	0.01	1	735	340	0.92	<5	2	113	<5	0.03	<10	<10	28	<10	397	1
85010	0.2	1.02	17	78	<0.5	<5	2.64	<1	6	34	6	2.33	<1	0.23	<10	0.53	1314	<2	0.01	1	673	26	0.56	<5	2	104	<5	<0.01	<10	<10	34	<10	69	2
85011	2.2	1.05	38	83	<0.5	<5	3.61	1	10	24	108	3.49	<1	0.25	<10	0.65	2520	5	0.01	1	899	22	1.39	<5	3	137	<5	<0.01	<10	<10	34	<10	110	2
85012	2.0	1.14	29	71	<0.5	<5	2.93	1	9	29	121	3.09	<1	0.20	<10	0.60	2299	13	0.01	1	849	36	1.12	<5	2	103	<5	0.01	<10	<10	39	<10	114	2
85013	0.5	1.08	10	240	<0.5	<5	2.88	<1	8	40	8	2.92	<1	0.29	<10	0.62	1983	<2	0.02	1	848	35	0.72	<5	2	105	<5	<0.01	<10	<10	30	<10	67	3
85014	2.7	0.91	39	127	<0.5	<5	3.25	7	9	48	55	3.45	<1	0.33	<10	0.68	1907	2	0.01	1	919	1704	1.04	<5	3	150	<5	<0.01	<10	<10	27	<10	794	3
85015	6.0	1.59	221	107	<0.5	<5	5.47	18	15	50	306	5.01	<1	0.18	<10	0.96	2606	13	0.01	6	1286	1330	2.40	<5	7	159	<5	0.04	<10	<10	91	14	1755	2
85016	4.4	1.94	93	99	<0.5	<5	5.01	13	14	49	349	5.59	<1	0.17	<10	1.27	2803	23	0.01	5	1467	420	2.34	<5	8	144	<5	0.03	<10	<10	92	12	1366	2
85017	5.3	2.18	93	113	<0.5	<5	6.64	9	16	40	434	5.80	<1	0.25	<10	1.76	3723	19	0.01	5	1449	552	1.72	<5	10	260	<5	0.02	<10	10	96	<10	885	2
85018	2.5	2.02	93	124	<0.5	<5	4.73	4	15	57	285	5.35	<1	0.23	<10	1.43	2060	29	0.01	5	1275	92	1.60	<5	11	125	<5	0.02	<10	<10	108	<10	440	2
85019	1.3	2.50	29	127	0.6	<5	6.10	<1	15	66	190	5.14	<1	0.37	<10	1.77	2223	18	0.05	7	1340	17	0.99	<5	15	139	<5	0.05	<10	<10	130	<10	106	3
85020	3.2	2.33	39	141	0.6	<5	3.66	1	24	77	431	5.31	<1	0.34	<10	1.47	1722	22	0.03	10	1492	24	1.17	<5	15	91	<5	0.05	<10	<10	142	<10	231	3
85021	<0.2	1.09	<5	65	<0.5	<5	2.64	<1	9	44	17	2.38	<1	0.29	14	0.72	661	3	0.05	3	902	14	0.28	<5	2	140	<5	<0.01	<10	<10	24	<10	72	4
85022	1.7	1.62	54	117	0.6	<5	5.79	2	19	134	199	5.43	<1	0.28	<10	1.12	2575	30	0.03	13	821	36	1.08	<5	10	147	<5	0.06	<10	<10	90	<10	181	4
85023	0.7	1.51	14	145	0.7	<5	3.16	<1	17	240	142	3.39	<1	0.29	<10	1.32	1327	36	0.05	22	1139	13	0.31	<5	8	103	<5	0.12	<10	<10	105	<10	92	4
85024	<0.2	1.18	<5	269	0.7	<5	2.20	<1	11	52	13	2.53	<1	0.25	12	0.78	394	<2	0.06	3	915	12	0.05	<5	3	63	<5	0.07	<10	<10	40	<10	65	7
85025	>200.0	0.87	1833	108	<0.5	52	4.64	39	65	24	2420	3.23	1	0.09	<10	0.26	962	117	0.05	26	870	431	0.79	367	2	157	<5	0.03	<10	<10	22	19	329	7
85026	<0.2	1.19	<5	416	0.5	<5	2.55	<1	9	63	11	2.46	<1	0.32	17	0.74	363	<2	0.06	4	928	16	0.05	<5	2	83	<5	0.01	<10	<10	35	<10	60	9
85027	4.7	1.69	250	114	<0.5	<5	3.47	12	13	51	278	4.43	<1	0.23	<10	1.10	1765	29	0.02	3	990	123	1.15	<5	6	126	<5	0.01	<10	<10	69	<10	743	2
85028	2.6	1.47	144	122	<0.5	<5	5.25	3	11	73	138	3.76	<1	0.27	<10	0.94	2257	22	0.02	3	896	25	1.17	<5	6	186	<5	0.01	<10	<10	57	<10	149	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2768RJ

Date : Aug-27-08

Ascot resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 14

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
85029	2.1	1.12	85	43	<0.5	<5	6.98	2	14	126	66	3.47	<1	0.19	<10	1.06	2211	25	0.01	12	572	96	1.87	<5	8	254	<5	0.01	<10	<10	53	<10	72	2
85030	2.1	1.47	19	145	0.6	<5	1.95	2	22	199	442	3.60	<1	0.15	<10	1.59	1005	37	0.03	21	1123	33	0.44	<5	5	78	<5	0.11	<10	<10	103	<10	263	3
85031	0.5	1.42	10	125	0.7	<5	2.48	<1	14	78	122	3.73	<1	0.12	<10	0.99	1096	34	0.04	3	860	16	0.36	<5	7	89	<5	0.12	<10	<10	77	<10	140	3
85032	1.3	1.71	11	95	0.7	<5	5.27	1	18	107	190	4.30	<1	0.14	<10	1.20	1571	26	0.04	9	1044	44	0.33	<5	8	128	<5	0.12	<10	<10	90	<10	205	4
85033	1.2	1.72	6	316	0.9	<5	4.11	1	21	119	219	4.63	<1	0.18	<10	1.59	1490	61	0.04	13	1132	30	0.29	<5	12	191	<5	0.11	<10	<10	109	<10	230	5
85034	<0.2	1.30	11	131	<0.5	<5	2.39	<1	30	56	8	2.79	<1	0.41	<10	0.74	828	3	0.03	6	715	8	1.02	<5	3	107	<5	<0.01	<10	<10	28	<10	50	4
85035	0.3	1.62	23	197	<0.5	<5	3.69	<1	16	36	121	3.82	<1	0.26	11	1.00	1231	21	0.03	2	947	8	0.60	<5	6	150	<5	0.02	<10	<10	55	<10	90	2
85036	<0.2	1.72	<5	252	0.5	<5	2.88	<1	13	47	57	3.67	<1	0.32	14	1.15	1107	24	0.04	2	985	10	0.30	<5	7	153	<5	0.04	<10	<10	61	<10	86	2
85037	1.9	1.61	50	189	<0.5	<5	3.34	12	19	50	227	4.32	<1	0.24	<10	0.92	1247	33	0.03	2	874	35	1.12	<5	6	138	<5	0.02	<10	<10	59	<10	1040	2
85038	0.5	1.63	16	151	0.6	<5	4.04	1	19	91	100	3.65	<1	0.35	13	1.02	1256	15	0.04	8	930	28	0.61	<5	8	124	<5	0.04	<10	<10	69	<10	175	3
85039	<0.2	1.03	<5	740	<0.5	<5	2.76	<1	8	40	4	1.77	<1	0.30	10	0.69	646	<2	0.03	5	739	7	0.22	<5	3	137	<5	<0.01	<10	<10	23	<10	54	4
85040	8.2	1.47	101	103	<0.5	<5	6.28	28	41	78	659	4.29	<1	0.23	<10	0.89	1655	24	0.03	4	826	78	1.59	<5	6	185	<5	0.03	<10	<10	57	18	2384	2
85041	0.6	1.34	1149	80	<0.5	<5	2.87	25	11	50	83	3.55	<1	0.25	<10	0.75	1276	12	0.01	2	818	11	0.57	<5	4	106	<5	<0.01	<10	<10	41	<10	116	2
85042	1.6	1.21	137	70	<0.5	<5	4.02	3	11	53	117	3.55	<1	0.21	<10	0.80	1633	12	0.01	3	759	28	1.00	<5	5	207	<5	<0.01	<10	<10	40	<10	131	2
85043	1.4	0.90	162	65	<0.5	<5	3.28	6	9	89	63	3.32	<1	0.17	<10	0.67	1307	25	0.01	2	603	99	1.51	<5	4	278	<5	<0.01	<10	<10	23	<10	270	1
85044	3.1	1.78	38	51	<0.5	<5	6.55	1	17	158	224	4.50	<1	0.11	<10	1.44	2267	16	0.01	16	1066	10	0.61	<5	13	162	<5	0.01	<10	<10	114	<10	205	2
85045	<0.2	0.93	<5	171	<0.5	<5	1.54	<1	8	47	2	2.12	<1	0.28	16	0.60	688	<2	0.03	4	757	13	0.27	<5	3	69	<5	<0.01	<10	<10	20	<10	178	5
85046	7.1	1.26	535	54	<0.5	5	1.98	113	12	47	261	7.88	<1	0.13	<10	0.98	1716	3	0.01	1	699	1111	>5.00	<5	3	79	<5	<0.01	<10	<10	44	95	>10000	3
85047	4.1	1.41	248	96	<0.5	<5	1.56	50	15	58	160	5.57	<1	0.16	<10	0.89	2049	5	0.01	2	985	801	2.44	<5	4	43	<5	<0.01	<10	<10	77	41	5784	2
85048	2.5	1.49	242	85	<0.5	<5	2.05	48	17	63	117	6.39	<1	0.22	<10	1.00	2023	11	0.01	2	995	707	3.88	<5	4	72	<5	<0.01	<10	<10	60	41	5699	2
85049	3.6	1.33	351	72	<0.5	<5	1.67	29	14	71	128	6.25	<1	0.15	<10	0.94	1778	6	0.01	1	820	889	4.02	<5	3	51	<5	<0.01	<10	<10	64	18	2445	3
85050	<0.2	0.94	<5	271	0.7	<5	0.48	<1	9	133	<1	2.20	<1	0.50	<10	0.60	624	<2	0.07	6	748	11	0.02	<5	2	46	<5	0.13	<10	<10	40	<10	89	2
85051	1.8	1.68	240	85	<0.5	<5	1.16	16	21	53	54	6.80	<1	0.19	<10	1.20	2130	14	0.01	2	1186	635	3.69	<5	5	49	<5	<0.01	<10	<10	80	13	1612	3
85052	2.7	1.35	290	68	<0.5	<5	1.69	18	17	98	46	6.21	<1	0.11	<10	1.02	2127	8	0.01	3	602	989	3.89	<5	3	61	<5	<0.01	<10	<10	61	12	1539	2
85053	2.5	1.63	124	75	<0.5	<5	1.89	15	15	51	93	5.53	<1	0.16	<10	1.03	1966	10	0.01	1	991	648	1.90	<5	5	59	<5	<0.01	<10	<10	81	14	1893	2
85054	3.7	0.97	189	99	<0.5	<5	4.32	12	23	50	80	4.25	<1	0.24	<10	0.59	1899	12	0.01	3	990	1769	1.47	<5	5	142	<5	<0.01	<10	<10	44	10	1228	2
85055	2.5	1.74	178	76	<0.5	<5	2.88	11	18	43	57	6.32	<1	0.16	<10	1.16	2184	7	0.01	1	995	1041	2.93	<5	5	80	<5	0.01	<10	<10	75	11	1247	2
85056	27.1	1.86	751	52	<0.5	6	2.46	57	11	44	99	9.79	<1	0.10	<10	1.46	2407	2	0.01	<1	876	>10000	>5.00	<5	4	53	<5	0.01	<10	10	68	44	5776	4
85057	3.8	1.96	464	83	<0.5	<5	0.90	21	14	46	65	7.23	<1	0.12	<10	1.46	2310	9	0.01	1	936	1421	3.70	<5	4	25	<5	0.01	<10	10	83	14	1731	3
85058	2.3	1.73	313	78	<0.5	<5	1.26	21	14	61	50	6.43	<1	0.12	<10	1.39	2311	3	0.01	2	853	1224	3.61	<5	4	30	<5	0.02	<10	<10	72	17	2140	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2768RJ

Date : Aug-27-08

Ascot resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 14

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
85059	0.7	1.53	97	76	<0.5	<5	1.32	11	10	53	33	4.87	<1	0.15	<10	1.07	1755	6	0.01	1	783	476	1.70	<5	3	44	<5	0.01	<10	<10	50	12	1402	2
85060	27.4	1.16	1181	26	<0.5	9	0.42	181	7	69	129	12.38	<1	0.06	<10	1.00	1395	<2	0.01	<1	472	>10000	>5.00	<5	1	12	<5	<0.01	<10	10	21	165	>10000	5
85061	2.4	1.14	143	121	<0.5	<5	1.27	20	9	83	18	4.89	<1	0.15	<10	1.00	1791	10	0.01	1	650	1312	2.47	<5	3	62	<5	<0.01	<10	<10	33	19	2538	2
85062	1.8	1.43	132	189	<0.5	<5	1.16	16	10	72	45	5.29	<1	0.19	<10	1.06	1810	6	0.01	2	817	1285	2.07	<5	3	48	<5	<0.01	<10	<10	41	16	2095	2
85063	2.9	1.56	277	104	<0.5	<5	1.78	16	11	54	51	6.17	<1	0.20	<10	1.13	2030	4	0.01	1	833	951	3.38	<5	3	74	<5	<0.01	<10	<10	47	13	1574	3
85064	2.8	1.77	270	111	<0.5	<5	1.49	28	16	76	132	6.51	<1	0.30	<10	1.08	2230	7	0.01	3	1239	666	3.85	<5	4	57	<5	<0.01	<10	<10	66	25	3333	3
85065	3.0	2.09	219	126	<0.5	<5	1.03	20	18	48	115	6.66	<1	0.28	<10	1.49	2805	8	0.01	2	1439	1038	3.30	<5	4	31	<5	0.01	<10	11	85	18	2244	3
85066	8.5	0.81	518	51	<0.5	<5	0.89	57	12	185	267	6.96	<1	0.24	<10	0.48	1374	9	0.01	5	962	3685	>5.00	<5	2	29	<5	0.01	<10	<10	37	55	7044	3
85067	4.6	1.59	313	111	<0.5	<5	1.25	19	18	54	226	6.27	<1	0.26	<10	1.09	3030	8	0.01	2	1252	910	4.11	<5	4	37	<5	0.01	<10	11	69	16	1993	2
85068	79.9	0.26	660	18	<0.5	<5	2.04	200	6	233	3396	12.16	<1	0.10	<10	0.35	1480	<2	0.01	4	453	>10000	>5.00	52	<1	112	<5	<0.01	<10	<10	6	196	>10000	5
85069	5.4	1.05	243	111	<0.5	<5	2.57	15	13	81	175	5.96	<1	0.23	<10	0.80	2702	6	0.01	3	906	987	4.09	<5	3	89	<5	<0.01	<10	<10	40	11	1342	2
85070	3.2	1.72	151	175	<0.5	<5	3.38	5	16	143	137	5.56	<1	0.36	<10	1.24	3490	5	0.01	6	1192	468	2.21	<5	4	138	<5	<0.01	<10	11	65	<10	389	2
85071	3.5	1.61	176	122	<0.5	<5	3.14	4	17	58	185	5.18	<1	0.31	<10	1.16	3407	10	0.01	4	1238	96	1.88	<5	4	106	<5	<0.01	<10	11	67	<10	261	2
85072	4.5	1.02	371	128	<0.5	<5	4.87	9	15	91	190	5.52	<1	0.31	<10	1.08	3622	4	0.01	4	1114	194	2.80	5	4	222	<5	<0.01	<10	<10	44	<10	371	2
85073	3.3	1.46	176	109	<0.5	<5	4.52	5	15	47	190	5.07	<1	0.27	<10	1.02	3196	4	0.01	3	1168	110	2.36	<5	3	116	<5	<0.01	<10	<10	60	<10	409	2
85074	6.3	0.73	129	84	<0.5	<5	6.00	5	9	185	34	3.36	<1	0.24	<10	0.46	3469	5	0.01	5	570	600	2.95	<5	1	164	<5	<0.01	<10	<10	25	<10	679	2
85075	2.9	2.31	629	248	1.2	169	11.68	13	53	170	502	7.41	9	0.27	17	0.47	1310	102	0.08	78	962	98	2.45	<5	5	151	<5	0.20	<10	<10	61	20	106	24
85076	4.1	1.86	134	205	<0.5	<5	1.75	4	16	148	182	5.60	<1	0.25	<10	1.35	3836	14	0.01	5	1135	388	1.89	<5	4	45	<5	0.01	<10	13	90	<10	561	2
85077	3.0	1.74	151	81	<0.5	5	5.44	5	15	52	175	5.07	<1	0.21	<10	1.16	3681	10	0.01	4	1059	163	1.98	<5	3	145	<5	<0.01	<10	10	77	<10	413	2
85078	2.6	1.88	130	123	<0.5	<5	3.88	4	17	67	160	5.91	<1	0.29	<10	1.23	3124	15	0.01	3	1276	259	2.02	<5	4	141	<5	<0.01	<10	<10	86	<10	404	2
85079	9.5	0.53	176	108	<0.5	<5	10.50	15	11	45	208	4.18	<1	0.16	<10	0.29	3366	19	0.01	2	851	1147	3.82	<5	2	176	<5	<0.01	<10	<10	40	13	1633	2
85080	3.1	1.68	92	159	<0.5	<5	3.83	5	16	111	289	5.61	<1	0.30	<10	0.93	2832	13	0.01	5	1121	208	2.49	<5	4	107	<5	<0.01	<10	<10	92	<10	736	2
85081	0.2	1.43	51	157	<0.5	<5	3.26	1	8	57	10	3.41	<1	0.35	11	0.82	1710	<2	0.02	2	934	22	0.61	<5	3	91	<5	<0.01	<10	<10	47	<10	92	3
85082	<0.2	1.48	38	142	<0.5	<5	2.96	<1	9	84	8	3.43	<1	0.36	12	0.85	1551	<2	0.02	2	949	13	0.55	<5	3	85	<5	<0.01	<10	<10	56	<10	80	3
85083	<0.2	1.42	36	130	<0.5	<5	2.90	<1	9	53	7	3.46	<1	0.35	12	0.84	1550	<2	0.02	2	956	11	0.66	<5	3	90	<5	<0.01	<10	<10	52	<10	77	3
85084	0.9	1.38	57	140	<0.5	<5	5.21	8	8	86	17	3.41	<1	0.32	13	0.75	2275	<2	0.01	2	787	693	0.93	<5	3	119	<5	<0.01	<10	<10	45	<10	909	3
85085	3.6	1.29	117	139	<0.5	<5	2.66	26	9	67	92	3.99	<1	0.27	<10	0.70	1833	<2	0.01	2	877	2293	1.69	<5	2	68	<5	0.01	<10	<10	55	21	2641	4
85086	3.4	1.91	367	110	0.5	<5	3.67	14	18	41	216	5.39	<1	0.22	<10	1.16	2943	12	0.01	2	1251	312	1.55	<5	4	78	<5	0.08	<10	<10	95	<10	959	2
85087	5.8	1.75	2349	97	<0.5	<5	3.66	59	19	38	281	6.02	<1	0.18	<10	1.09	3374	9	0.01	3	1195	387	2.68	14	4	60	<5	0.06	<10	10	95	<10	1023	2
85088	4.4	1.67	75	108	0.8	<5	3.34	3	19	39	215	4.59	<1	0.25	<10	0.92	2820	14	0.02	3	1362	168	1.45	<5	5	81	<5	0.12	<10	<10	92	<10	410	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2768RJ

Date : Aug-27-08

Ascot resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 14

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
85089	3.8	1.89	91	113	1.0	<5	3.72	2	20	37	229	4.77	<1	0.31	<10	1.03	2437	5	0.02	3	1342	48	1.10	<5	5	99	<5	0.14	<10	<10	100	<10	209	3
85090	5.8	1.57	262	122	0.7	<5	3.55	8	18	35	362	4.95	<1	0.30	<10	0.73	2295	10	0.01	4	1226	246	1.91	<5	4	81	<5	0.08	<10	<10	75	<10	479	2
85091	6.2	1.43	369	146	0.5	<5	3.28	14	15	50	252	4.36	<1	0.35	<10	0.66	2542	6	0.01	5	1037	718	1.92	<5	3	71	<5	0.06	<10	<10	56	12	1392	2
85092	11.0	1.31	239	98	<0.5	<5	3.40	7	18	54	518	5.78	<1	0.29	<10	0.64	3294	20	0.01	5	944	241	4.21	<5	3	83	<5	0.01	<10	<10	45	<10	543	2
85093	12.7	0.64	595	121	<0.5	<5	5.38	28	12	50	126	3.54	<1	0.29	<10	0.25	2730	19	0.01	3	752	3253	3.74	9	2	133	<5	<0.01	<10	<10	19	25	3297	2
85094	4.6	0.60	405	121	<0.5	<5	5.40	11	11	45	190	4.21	<1	0.22	<10	0.40	3193	10	0.01	2	912	305	3.97	<5	3	128	<5	<0.01	<10	<10	40	<10	553	2
85095	8.7	0.44	147	134	<0.5	<5	5.79	7	14	40	271	3.74	<1	0.28	<10	0.62	3611	9	0.01	3	919	292	2.50	32	5	279	<5	<0.01	<10	<10	23	<10	510	1
85096	11.3	1.31	187	107	<0.5	<5	3.52	7	15	40	499	5.30	<1	0.20	<10	0.93	4888	5	0.01	3	1160	365	3.59	<5	4	83	<5	0.01	<10	16	73	<10	771	2
85097	24.5	0.46	454	102	<0.5	<5	12.16	40	12	20	470	5.27	<1	0.22	<10	0.53	5520	7	0.01	2	872	3559	>5.00	99	3	562	<5	<0.01	<10	11	19	35	4491	2
85098	7.1	0.69	227	138	<0.5	<5	5.34	19	11	54	279	4.21	<1	0.18	<10	0.57	2529	19	0.01	3	795	1400	3.35	6	3	151	<5	<0.01	<10	<10	42	17	2232	2
85099	5.6	1.34	1193	101	<0.5	<5	3.49	51	13	58	288	6.15	<1	0.18	<10	0.80	2210	37	0.01	2	838	1141	4.35	<5	5	92	<5	0.01	<10	<10	66	30	4032	2
85100	<0.2	1.09	<5	293	0.9	<5	0.61	<1	10	141	<1	2.38	<1	0.55	12	0.67	692	2	0.08	6	812	17	0.02	<5	3	57	5	0.15	<10	<10	45	<10	78	2
85101	3.8	1.79	93	123	<0.5	<5	5.00	11	14	57	342	5.36	<1	0.22	<10	0.95	2686	36	0.01	4	490	400	1.79	<5	7	120	<5	0.02	<10	<10	91	11	1431	2
85102	2.5	1.64	25	95	0.8	<5	3.00	1	16	78	249	4.33	<1	0.22	<10	0.98	1614	23	0.02	3	899	132	0.79	<5	6	74	<5	0.14	<10	<10	79	<10	187	3
85103	1.1	1.61	15	73	0.7	<5	2.58	<1	16	69	136	4.10	<1	0.17	<10	1.02	1279	18	0.03	3	911	15	0.62	<5	6	61	<5	0.13	<10	<10	73	<10	114	3
85104	1.2	1.59	60	72	0.7	<5	3.75	1	16	65	143	4.14	<1	0.16	<10	1.07	1640	17	0.02	3	884	59	0.78	<5	6	72	<5	0.12	<10	<10	74	<10	124	3
85105	1.1	1.69	<5	115	0.9	<5	2.12	<1	17	60	147	3.91	<1	0.13	<10	1.27	1188	18	0.03	3	1009	10	0.28	<5	5	69	<5	0.15	<10	<10	72	<10	123	3
85106	<0.2	1.08	<5	80	0.5	<5	2.39	<1	8	36	3	2.18	<1	0.32	17	0.63	455	<2	0.04	3	933	10	0.17	<5	2	93	<5	0.01	<10	<10	25	<10	44	6
85107	0.4	1.33	8	87	0.5	<5	2.64	<1	11	44	103	2.47	<1	0.37	17	0.73	743	<2	0.05	3	965	10	0.36	<5	3	130	<5	<0.01	<10	<10	28	<10	70	4
85108	1.9	2.02	22	114	0.6	<5	4.31	<1	15	71	235	4.64	<1	0.29	10	1.23	1703	46	0.02	3	1164	22	0.72	<5	7	119	<5	0.05	<10	<10	82	<10	141	3
85109	2.5	1.89	32	102	0.6	<5	4.04	<1	16	47	247	4.29	<1	0.25	<10	1.19	1617	32	0.02	2	1024	10	0.88	<5	5	166	<5	0.09	<10	<10	71	<10	106	3
85110	4.0	1.78	147	98	<0.5	<5	3.94	3	14	87	286	4.28	<1	0.28	<10	1.10	1919	35	0.02	5	975	31	0.98	<5	6	112	<5	0.03	<10	<10	70	<10	170	2
85111	2.9	1.69	64	99	<0.5	<5	4.32	3	15	62	203	4.59	<1	0.26	<10	1.06	2023	21	0.02	4	1032	50	1.47	<5	7	142	<5	0.03	<10	<10	76	<10	285	2
85112	3.6	2.06	68	61	<0.5	<5	8.41	3	22	141	232	5.17	<1	0.18	<10	1.76	2718	15	0.01	17	1100	115	1.89	<5	13	233	<5	0.03	<10	<10	113	<10	222	3
85113	4.5	2.86	50	288	0.7	<5	4.32	2	52	240	646	7.62	<1	0.31	<10	2.70	1877	15	0.04	29	1326	161	2.20	<5	17	148	<5	0.13	<10	<10	172	<10	262	5
85114	1.3	2.91	27	215	0.9	<5	4.44	<1	36	255	308	6.98	<1	0.66	<10	2.69	1712	22	0.05	33	1434	32	0.83	<5	15	189	<5	0.17	<10	<10	161	<10	187	5
85115	<0.2	1.36	<5	62	<0.5	<5	3.19	<1	9	46	9	2.21	<1	0.35	12	0.90	910	<2	0.04	6	727	11	0.23	<5	4	96	<5	0.01	<10	<10	33	<10	55	3
85116	1.5	3.31	38	264	0.9	<5	6.31	<1	31	257	237	6.73	<1	0.79	<10	3.59	2124	15	0.05	32	1445	23	0.92	<5	20	223	<5	0.14	<10	<10	176	<10	170	6
85117	1.9	2.29	24	336	0.9	<5	3.52	1	33	241	354	6.14	<1	0.57	<10	2.56	1390	21	0.05	32	1592	44	0.55	<5	10	165	<5	0.18	<10	<10	159	<10	208	5
85118	1.4	2.24	14	267	0.8	<5	4.43	2	25	233	216	5.67	<1	0.39	<10	2.82	1628	15	0.04	28	1414	43	0.34	<5	13	260	<5	0.14	<10	<10	147	<10	281	5

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2768RJ**

Date : Aug-27-08

Ascot resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 14

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
85119	1.1	2.32	11	632	0.8	<5	5.72	1	24	237	170	5.66	<1	0.42	<10	2.67	1995	13	0.04	30	1211	35	0.33	<5	18	293	<5	0.09	<10	<10	168	<10	232	4
85120	2.1	2.25	35	77	0.6	<5	5.56	2	25	217	161	5.13	<1	0.16	<10	2.39	2141	16	0.02	27	1232	90	0.64	<5	15	248	<5	0.07	<10	<10	150	<10	279	4
85121	2.7	2.45	52	121	0.8	<5	6.21	6	31	247	223	5.36	<1	0.11	<10	2.63	2551	14	0.02	32	1595	128	0.77	<5	17	184	<5	0.11	<10	<10	187	<10	593	3
85122	3.9	1.04	74	29	<0.5	<5	>15.00	2	14	139	137	2.67	<1	0.05	<10	0.90	5197	10	0.01	15	909	10	0.45	<5	10	211	<5	<0.01	<10	<10	99	<10	118	1
85123	7.7	2.27	212	45	<0.5	<5	5.15	156	28	228	258	8.84	1	0.07	<10	2.10	3203	12	0.01	26	1280	3074	>5.00	<5	18	80	<5	0.06	<10	10	167	143	>10000	4
85124	5.4	2.63	62	46	0.8	<5	5.92	17	30	243	373	5.60	<1	0.07	<10	2.71	2999	35	0.01	31	1426	575	0.98	<5	18	137	<5	0.13	<10	<10	182	14	1515	4
85125	2.0	1.71	5563	246	0.6	9	7.37	123	178	64	96	4.65	<1	0.15	18	0.40	1219	13	0.13	33	1301	556	1.59	<5	3	134	<5	0.11	<10	<10	66	<10	368	16
85126	2.3	1.68	31	53	0.8	<5	2.88	2	23	169	256	3.83	<1	0.08	<10	1.77	1186	58	0.03	20	1243	39	0.43	<5	7	96	<5	0.17	<10	<10	119	<10	301	3
85127	1.7	1.80	106	109	0.8	<5	2.24	4	27	197	280	3.81	<1	0.19	<10	2.11	1033	67	0.04	24	1286	102	0.35	<5	6	59	<5	0.17	<10	<10	118	<10	299	3
85128	4.4	2.09	1083	93	0.9	<5	4.59	28	26	163	481	5.02	<1	0.17	<10	1.97	2537	56	0.02	21	1342	411	0.96	10	13	101	<5	0.15	<10	<10	150	<10	712	4
85129	8.1	1.66	1849	48	0.5	<5	5.47	54	22	190	319	5.46	<1	0.06	<10	1.41	2560	13	0.01	22	1018	935	2.24	10	14	93	<5	0.07	<10	<10	139	13	1568	3
85130	3.0	2.04	2107	38	<0.5	<5	7.59	77	25	249	136	5.24	1	0.05	<10	1.76	3048	11	0.01	32	1270	3852	1.11	18	17	140	<5	0.06	<10	<10	172	26	3239	3
85131	2.2	1.97	54	37	0.6	<5	5.95	2	25	206	224	4.31	<1	0.06	<10	1.90	2505	65	0.01	27	1224	35	0.44	<5	12	115	<5	0.10	<10	<10	141	<10	180	4
85132	5.0	1.09	102	22	<0.5	<5	4.75	13	14	163	284	3.21	<1	0.04	<10	1.10	1866	189	0.01	14	571	666	1.34	<5	6	84	<5	0.03	<10	<10	69	10	1293	2
85133	5.3	2.13	59	34	0.6	<5	5.00	3	27	218	328	4.78	<1	0.05	<10	2.21	2236	100	0.01	28	1182	11	0.67	<5	8	123	<5	0.11	<10	<10	142	<10	255	3
85134	11.2	1.90	167	29	0.5	<5	6.79	9	25	212	778	4.62	<1	0.05	<10	1.79	2472	116	0.01	26	1072	567	0.91	<5	12	129	<5	0.09	<10	<10	137	10	675	3
85135	4.1	1.70	61	50	0.5	<5	4.97	4	25	270	354	4.95	1	0.07	<10	1.51	1982	53	0.01	29	1137	56	0.77	<5	15	144	<5	0.08	<10	<10	154	<10	430	3
85136	3.5	1.50	46	72	0.6	<5	4.88	2	25	193	222	3.75	<1	0.09	<10	1.49	1657	20	0.01	24	1275	19	0.59	<5	9	110	<5	0.11	<10	<10	118	<10	237	4
85137	4.2	1.20	110	44	<0.5	<5	6.27	5	23	148	208	4.98	<1	0.15	<10	1.92	2501	24	0.01	24	1056	43	1.58	11	14	513	<5	0.02	<10	<10	88	<10	280	2
85138	1.6	1.78	29	98	<0.5	<5	7.86	2	23	205	210	4.78	<1	0.07	<10	1.56	2275	31	0.01	24	1244	15	0.35	<5	17	315	<5	0.04	<10	<10	135	<10	229	3
85139	2.9	1.68	33	53	0.5	<5	6.75	2	23	186	301	4.75	<1	0.06	<10	1.51	2082	26	0.02	24	1216	13	0.45	<5	13	277	<5	0.08	<10	<10	129	<10	243	4
85140	2.4	1.68	44	60	0.5	<5	5.65	2	24	190	198	4.52	<1	0.09	<10	1.60	2081	33	0.02	26	1302	30	0.70	<5	12	180	<5	0.08	<10	<10	131	<10	227	4
85141	2.6	1.54	37	51	0.5	<5	5.63	3	23	225	408	4.48	<1	0.10	<10	1.59	1865	36	0.02	34	1309	23	0.42	<5	11	148	<5	0.09	<10	<10	125	<10	284	4
85142	2.7	1.76	45	50	<0.5	<5	7.12	3	26	203	348	5.19	1	0.07	<10	1.58	2090	35	0.02	27	1261	27	0.69	<5	15	173	<5	0.07	<10	<10	145	<10	298	4
85153	<0.2	0.90	31	105	<0.5	<5	2.73	<1	9	71	53	3.17	<1	0.21	<10	0.65	1077	4	0.01	1	641	12	0.90	<5	4	97	<5	<0.01	<10	<10	37	<10	58	1
85154	<0.2	1.20	27	66	<0.5	<5	4.45	<1	10	56	32	3.55	<1	0.18	<10	0.77	1557	2	0.02	1	743	17	0.92	<5	5	115	<5	<0.01	<10	<10	51	<10	69	2
85155	<0.2	0.82	45	84	<0.5	<5	2.96	1	9	82	19	3.05	<1	0.23	<10	0.60	1144	4	0.01	1	675	17	1.03	<5	3	106	<5	<0.01	<10	<10	29	<10	159	1
85156	0.2	1.14	80	172	<0.5	<5	1.89	2	8	101	13	3.11	<1	0.46	<10	0.50	1074	2	0.01	2	735	15	1.05	<5	2	64	<5	<0.01	<10	<10	30	<10	165	3
85157	0.5	1.28	113	176	<0.5	<5	2.80	3	8	64	7	3.15	<1	0.50	<10	0.57	1416	2	0.01	1	787	17	1.17	<5	2	76	<5	<0.01	<10	<10	32	<10	169	4
85158	1.1	1.19	140	121	<0.5	<5	1.71	10	11	59	24	4.09	<1	0.38	<10	0.55	1222	2	0.01	2	729	245	2.48	<5	2	31	<5	<0.01	<10	<10	29	<10	1036	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2768RJ

Date : Aug-27-08

Ascot resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 14

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
85159	12.6	1.48	954	27	<0.5	8	0.63	176	8	63	161	11.73	<1	0.09	<10	1.19	1688	<2	<0.01	<1	554	3945	>5.00	<5	2	16	<5	<0.01	<10	<10	35	165	>10000	5
85160	7.9	1.52	848	33	<0.5	8	0.91	179	9	57	223	11.18	<1	0.12	<10	1.12	1622	<2	0.01	<1	607	2577	>5.00	<5	2	20	<5	<0.01	<10	<10	31	160	>10000	4
85161	0.6	1.13	103	101	<0.5	<5	1.32	7	9	109	21	3.81	<1	0.21	<10	0.69	1127	6	0.01	3	671	181	1.22	<5	3	44	<5	<0.01	<10	<10	33	<10	766	2
85162	0.2	0.72	46	74	<0.5	<5	2.21	1	9	108	15	3.22	<1	0.21	<10	0.61	1258	5	0.01	3	651	38	0.77	<5	3	90	<5	<0.01	<10	<10	21	<10	148	2
85163	1.0	1.01	121	94	<0.5	<5	2.07	6	9	131	16	4.31	<1	0.23	<10	0.80	1580	5	0.01	3	731	462	1.50	<5	4	72	<5	<0.01	<10	<10	29	<10	541	2
85164	9.9	0.45	110	77	<0.5	<5	1.89	84	8	141	253	4.40	<1	0.18	<10	0.66	1620	5	0.01	4	570	>10000	3.18	<5	3	114	<5	<0.01	<10	<10	11	81	>10000	2
85165	3.6	0.40	76	198	<0.5	<5	3.54	24	7	198	83	4.13	<1	0.27	<10	0.84	2076	7	0.02	5	657	820	1.57	<5	4	214	<5	<0.01	<10	<10	12	22	2834	2
85166	1.7	0.59	53	272	<0.5	<5	3.21	12	8	103	48	3.83	<1	0.24	<10	0.77	1734	3	0.01	3	740	678	1.12	<5	3	133	<5	<0.01	<10	<10	16	12	1561	2
85167	0.9	1.11	89	102	<0.5	<5	1.63	8	11	39	24	4.67	<1	0.25	<10	0.96	1613	10	0.01	1	889	344	1.54	<5	4	67	<5	<0.01	<10	<10	34	<10	919	2
85213	3.3	0.28	184	81	<0.5	<5	4.05	32	8	55	82	3.26	<1	0.17	<10	0.37	1611	2	0.01	2	520	896	3.11	<5	2	180	<5	<0.01	<10	<10	11	24	3231	1
85214	1.6	0.60	77	97	<0.5	<5	4.82	5	11	74	95	3.19	<1	0.18	<10	0.43	1872	9	0.01	6	662	239	1.13	<5	4	199	<5	<0.01	<10	<10	28	<10	490	1
85215	3.0	0.29	127	104	<0.5	<5	3.30	23	16	64	185	3.69	<1	0.25	<10	0.57	1653	14	0.01	5	847	262	2.21	<5	3	195	<5	<0.01	<10	<10	8	16	2150	1
85216	2.0	0.46	137	104	<0.5	<5	4.27	7	13	34	151	4.34	<1	0.26	<10	0.91	2146	9	0.01	2	885	139	1.58	<5	4	253	<5	<0.01	<10	<10	16	<10	487	2
85217	2.0	0.29	116	189	<0.5	<5	5.64	6	10	53	128	3.56	<1	0.22	<10	0.74	2507	5	0.01	3	688	171	1.76	<5	3	390	<5	<0.01	<10	<10	7	<10	467	1
85218	2.4	0.43	169	109	<0.5	<5	6.72	7	10	55	67	3.40	<1	0.20	<10	0.36	2036	7	0.01	3	552	242	2.51	<5	3	362	<5	<0.01	<10	<10	8	<10	439	1
85219	2.9	0.20	156	86	<0.5	<5	8.22	12	6	66	75	2.76	<1	0.15	<10	0.26	2125	4	0.01	2	448	640	2.57	<5	2	412	<5	<0.01	<10	<10	6	<10	1031	1
85220	1.5	1.16	40	132	<0.5	<5	10.18	4	11	46	126	3.32	<1	0.16	<10	0.83	2473	7	0.01	4	749	109	1.10	<5	5	274	<5	<0.01	<10	<10	48	<10	416	1
85221	1.8	0.85	62	162	<0.5	<5	8.77	4	18	46	155	3.18	<1	0.17	<10	0.70	2196	4	0.01	3	666	127	1.56	<5	5	217	<5	<0.01	<10	<10	36	<10	355	1
85222	1.0	1.01	80	73	<0.5	<5	8.38	3	8	35	23	3.36	<1	0.11	<10	0.80	2492	6	0.01	2	561	90	1.41	<5	4	257	<5	<0.01	<10	<10	40	<10	277	1
85223	0.5	0.61	61	11	<0.5	<5	1.74	3	5	5	15	2.40	<1	0.02	<10	0.59	1075	5	<0.01	<1	219	52	1.09	<5	1	34	<5	<0.01	<10	<10	20	<10	254	1
85224	6.8	0.72	168	86	<0.5	<5	2.59	21	14	91	241	4.28	<1	0.24	<10	1.05	1585	15	0.02	47	671	1394	3.07	5	3	115	<5	0.01	<10	<10	31	20	2213	2
85225	>200.0	0.95	1574	118	<0.5	46	4.56	37	55	75	2007	3.08	1	0.16	<10	0.27	986	104	0.06	23	733	378	0.68	294	2	142	<5	0.04	<10	<10	23	14	311	6
85226	3.8	0.19	277	42	<0.5	<5	3.07	48	9	93	68	5.85	<1	0.11	<10	0.88	1757	<2	<0.01	3	301	1139	>5.00	<5	2	192	<5	<0.01	<10	<10	5	40	5012	2
85227	2.8	0.72	164	84	<0.5	<5	1.75	8	8	101	33	3.53	<1	0.14	<10	0.83	1537	7	0.01	3	522	290	1.43	<5	3	91	<5	<0.01	<10	<10	25	<10	584	2
85228	1.0	3.44	92	52	<0.5	<5	5.86	13	33	301	106	6.18	<1	0.02	<10	3.29	2271	<2	0.01	36	1378	83	0.33	<5	26	253	<5	<0.01	<10	<10	264	27	1144	6
85229	2.6	0.61	431	73	<0.5	<5	2.76	13	10	60	58	6.35	<1	0.14	<10	0.81	1639	6	0.01	1	566	548	>5.00	<5	4	174	<5	<0.01	<10	<10	27	15	568	6
85230	<0.2	1.01	7	81	<0.5	<5	2.47	<1	11	53	<1	2.00	<1	0.25	10	0.72	621	2	0.03	4	620	11	0.52	<5	3	77	<5	<0.01	<10	<10	29	<10	87	5
85231	<0.2	1.06	<5	779	<0.5	<5	2.75	<1	6	43	<1	1.51	<1	0.24	15	0.71	481	<2	0.03	4	626	<2	0.08	<5	3	86	<5	<0.01	<10	<10	27	<10	71	6
139218	5.2	2.92	40	70	0.5	<5	6.28	3	27	60	80	5.89	<1	0.10	<10	2.07	2528	<2	0.01	12	1319	276	0.43	<5	16	142	<5	0.10	<10	<10	206	12	344	6
139219	1.8	2.37	43	59	0.6	<5	9.93	5	27	51	159	5.51	<1	0.12	<10	1.74	2620	<2	0.01	10	1159	56	0.63	<5	14	150	<5	0.11	<10	<10	156	<10	366	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2768RJ**

Date : Aug-27-08

Ascot resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 14

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139220	2.4	2.99	115	66	0.6	<5	4.70	13	32	66	114	6.90	<1	0.09	<10	2.47	2300	<2	0.01	13	1248	95	1.33	<5	19	90	<5	0.11	<10	<10	197	11	1021	3
139221	2.6	2.08	132	55	<0.5	<5	9.74	27	22	44	106	6.17	<1	0.08	<10	1.49	2975	<2	0.01	9	1067	269	2.37	<5	15	179	<5	0.03	<10	<10	143	19	2292	3
139222	0.7	3.05	89	44	0.5	<5	5.63	4	28	97	56	7.07	<1	0.05	<10	2.51	2521	<2	0.01	17	1222	61	1.20	<5	26	152	<5	0.08	<10	<10	242	<10	373	3
139223	3.4	2.86	74	63	<0.5	<5	5.45	43	40	41	165	7.28	<1	0.13	<10	1.95	2517	<2	0.01	14	1248	274	1.70	<5	13	116	<5	0.06	<10	<10	171	18	2140	3
139224	2.1	2.94	216	48	<0.5	6	3.79	13	44	66	56	9.61	<1	0.05	<10	2.24	2556	<2	<0.01	9	1152	199	4.56	<5	16	92	<5	0.01	<10	<10	197	10	1004	4
139225	2.0	2.01	170	76	<0.5	5	5.62	26	26	155	52	6.86	<1	0.12	<10	1.54	2722	<2	0.01	24	1318	215	2.71	<5	14	121	<5	<0.01	<10	<10	130	18	2258	3
139226	1.4	2.21	1183	68	<0.5	<5	5.23	29	29	266	93	5.44	1	0.07	<10	2.11	2780	<2	0.01	33	1442	103	1.24	5	21	131	<5	0.02	<10	<10	196	<10	353	3
139227	1.8	1.95	82	52	<0.5	<5	9.78	3	29	226	132	4.93	<1	0.07	<10	1.75	2712	2	0.01	32	1285	63	0.98	<5	23	208	<5	0.02	<10	<10	171	<10	200	3
139228	1.8	1.95	307	64	0.5	<5	7.03	10	33	251	138	5.08	<1	0.08	<10	1.55	2692	3	0.01	34	1377	105	1.28	<5	23	159	<5	0.05	<10	<10	189	<10	423	3
139229	0.5	0.82	34	102	<0.5	<5	2.64	1	11	46	50	2.88	<1	0.33	<10	0.66	1306	12	0.01	3	824	36	0.68	<5	4	147	<5	<0.01	<10	<10	24	<10	131	1
139230	3.6	2.12	6451	55	<0.5	<5	7.98	156	29	203	147	6.32	<1	0.09	<10	1.79	2988	<2	0.01	30	1206	130	2.29	38	18	200	<5	0.01	<10	<10	160	<10	649	3
139231	2.4	1.86	473	74	<0.5	<5	6.01	12	35	183	138	5.17	<1	0.14	<10	1.54	2131	4	0.01	32	1402	263	1.86	<5	17	143	<5	0.01	<10	<10	156	<10	234	2
139232	<0.2	2.11	189	73	<0.5	<5	4.89	5	22	93	89	4.73	1	0.07	<10	1.82	2048	<2	0.02	17	1281	52	0.48	<5	17	126	<5	<0.01	<10	<10	215	<10	204	2
139233	<0.2	1.80	137	59	<0.5	<5	5.14	3	27	90	77	4.80	1	0.05	<10	1.65	1723	<2	0.02	18	1218	53	1.62	<5	15	128	<5	<0.01	<10	<10	206	<10	121	2
139234	<0.2	2.40	274	77	<0.5	<5	2.56	6	24	95	77	5.56	<1	0.05	<10	2.17	1636	<2	0.02	20	1250	54	0.97	<5	17	64	<5	<0.01	<10	<10	216	<10	171	3
139235	<0.2	2.96	109	73	<0.5	<5	3.59	7	34	286	153	6.33	1	0.05	<10	2.65	2009	<2	0.01	37	1578	58	0.58	<5	28	119	<5	<0.01	<10	<10	267	<10	591	3
139236	<0.2	2.83	150	96	<0.5	<5	1.74	10	28	148	139	5.70	1	0.15	<10	2.60	1695	<2	0.01	24	1475	97	0.31	<5	13	41	<5	<0.01	<10	<10	193	<10	737	3
139237	<0.2	3.07	147	96	<0.5	<5	2.93	11	26	212	152	6.05	<1	0.12	<10	2.86	1826	<2	0.01	32	1582	131	0.24	<5	14	69	<5	0.01	<10	<10	182	<10	780	3
139238	<0.2	2.53	79	107	<0.5	<5	2.42	4	28	162	80	5.75	<1	0.11	15	2.20	1438	<2	0.02	25	1937	27	0.40	<5	11	65	<5	0.01	<10	<10	163	<10	494	4
139239	<0.2	2.58	79	123	<0.5	<5	3.91	2	30	221	93	5.68	1	0.10	<10	2.30	1875	<2	0.01	30	1592	34	0.62	<5	16	113	<5	0.01	<10	<10	217	<10	225	3
139240	0.2	2.52	70	240	<0.5	<5	5.24	3	27	171	56	5.44	<1	0.13	<10	2.26	1991	<2	0.01	25	1430	266	0.64	<5	15	180	<5	<0.01	<10	<10	170	<10	286	2
139241	0.9	2.79	139	91	<0.5	<5	3.30	7	25	186	218	5.82	<1	0.14	<10	2.47	2218	<2	0.01	29	1454	174	0.32	<5	15	89	<5	0.01	<10	<10	203	<10	449	2
139242	4.9	2.19	895	109	<0.5	<5	4.54	43	25	111	367	5.05	<1	0.17	<10	1.87	2070	<2	0.01	20	1250	3287	1.16	<5	10	114	<5	<0.01	<10	<10	147	16	2036	2
139243	<0.2	2.14	137	78	<0.5	<5	0.99	10	23	85	96	4.86	1	0.11	<10	1.92	1419	<2	0.01	16	1199	372	0.38	<5	9	21	<5	<0.01	<10	<10	163	<10	748	2
139244	0.3	2.21	183	138	<0.5	<5	0.74	6	27	88	103	5.02	1	0.11	<10	2.06	1494	<2	0.02	17	1213	155	0.28	<5	10	17	<5	0.01	<10	<10	170	<10	357	2
139245	<0.2	2.69	68	100	<0.5	<5	1.88	3	26	103	124	5.74	<1	0.09	<10	2.51	1709	<2	0.02	21	1456	45	0.30	<5	14	46	<5	0.01	<10	<10	222	<10	292	2
139246	<0.2	1.70	44	111	<0.5	<5	7.98	1	23	107	72	5.00	<1	0.09	<10	2.97	2153	<2	0.01	18	1093	19	0.81	<5	21	483	<5	<0.01	<10	<10	159	<10	145	2
139247	<0.2	2.65	95	93	0.5	<5	3.76	2	31	161	100	5.94	<1	0.06	<10	3.07	1788	<2	0.01	24	1457	12	0.94	<5	25	129	<5	0.06	<10	<10	234	<10	106	4
139248	<0.2	2.72	73	242	<0.5	<5	2.59	1	32	187	104	6.39	1	0.09	<10	3.02	2037	<2	0.01	27	1515	8	0.47	<5	26	90	<5	<0.01	<10	<10	249	<10	95	3
139249	<0.2	1.28	49	196	<0.5	<5	5.22	1	29	101	81	5.24	<1	0.16	<10	2.55	1597	<2	0.01	21	1298	9	1.15	<5	26	291	<5	<0.01	<10	<10	133	<10	93	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2768RJ

Date : Aug-27-08

Ascot resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 14

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139250	0.3	0.81	130	204	<0.5	<5	6.19	2	30	60	76	5.14	<1	0.20	<10	2.67	1926	6	0.01	21	1200	9	0.97	<5	25	458	<5	<0.01	<10	<10	84	<10	57	2
139251	0.5	0.48	218	236	<0.5	<5	5.73	4	27	46	81	4.93	<1	0.23	<10	2.14	1769	<2	0.01	21	1171	18	1.25	<5	22	357	<5	<0.01	<10	<10	50	<10	86	2
139252	0.6	0.50	279	301	<0.5	<5	6.63	6	25	45	72	5.07	<1	0.23	<10	2.52	1820	<2	0.01	21	1072	16	1.04	<5	19	412	<5	<0.01	<10	<10	51	<10	99	2
139253	1.7	0.47	269	413	<0.5	<5	4.88	5	32	59	95	5.17	<1	0.23	<10	2.03	2027	<2	0.01	29	1201	82	0.45	<5	25	296	<5	<0.01	<10	<10	51	<10	72	2
139254	1.6	0.46	116	247	<0.5	<5	7.34	2	32	53	66	5.43	<1	0.24	<10	2.35	2445	<2	0.01	31	1380	19	1.29	6	31	383	<5	<0.01	<10	<10	43	<10	81	2
139255	0.4	0.89	106	492	<0.5	<5	8.15	2	27	121	72	4.93	<1	0.19	<10	2.53	2394	<2	0.01	24	1241	7	0.64	<5	24	491	<5	<0.01	<10	<10	103	<10	48	2
139268	35.9	0.44	212	138	<0.5	<5	0.12	8	6	72	40	4.07	1	0.18	<10	0.12	131	6	0.01	1	622	356	2.69	11	2	6	<5	<0.01	<10	<10	11	<10	670	2
139269	47.0	0.54	209	114	<0.5	<5	0.24	10	6	92	42	4.41	<1	0.18	<10	0.19	251	4	0.01	2	660	341	3.21	11	1	10	<5	<0.01	<10	<10	12	<10	1034	2
139270	57.2	0.49	185	144	<0.5	<5	0.29	7	6	64	47	4.05	<1	0.19	<10	0.13	203	7	0.01	1	640	311	2.44	7	2	11	<5	<0.01	<10	<10	13	<10	641	2
139271	25.1	0.89	116	223	0.5	<5	0.20	4	8	48	29	4.21	<1	0.21	<10	0.35	383	4	0.01	<1	900	325	1.89	6	2	6	<5	<0.01	<10	<10	17	<10	397	2
139272	8.8	0.51	518	135	<0.5	<5	0.51	12	7	96	30	3.92	<1	0.21	<10	0.16	318	3	0.01	3	687	166	2.57	<5	1	14	<5	<0.01	<10	<10	10	<10	218	2
139273	>200.0	0.33	396	75	<0.5	<5	1.80	53	4	132	141	4.02	5	0.14	<10	0.09	313	3	0.01	1	373	4647	3.88	91	1	47	<5	<0.01	<10	<10	5	60	7557	2
139274	49.7	0.53	355	54	<0.5	<5	0.19	27	10	106	104	7.62	2	0.18	<10	0.16	187	3	0.01	1	798	555	>5.00	12	1	5	<5	<0.01	<10	<10	11	20	2413	3
139275	24.0	0.56	256	71	<0.5	<5	0.28	13	9	108	76	6.96	1	0.18	<10	0.19	219	3	0.01	1	744	282	>5.00	8	1	6	<5	<0.01	<10	<10	12	10	1173	3
139276	11.5	0.63	197	108	<0.5	<5	0.21	9	6	104	69	5.07	<1	0.18	<10	0.21	302	<2	0.01	1	690	244	2.76	5	1	5	<5	0.01	<10	<10	14	<10	736	2
139277	40.0	0.34	322	99	<0.5	<5	0.05	8	4	120	49	3.43	<1	0.15	<10	0.07	174	3	0.01	1	525	242	0.67	11	1	2	<5	<0.01	<10	<10	7	<10	267	1
139278	18.7	0.27	485	138	<0.5	<5	0.02	11	2	71	11	3.35	1	0.22	<10	0.02	19	<2	0.01	<1	677	190	0.53	9	1	3	<5	0.01	<10	<10	4	<10	202	2
139279	7.0	1.56	155	139	<0.5	<5	0.73	6	17	58	52	5.31	<1	0.26	<10	0.78	986	<2	0.01	4	854	111	2.79	<5	2	27	<5	<0.01	<10	<10	40	<10	420	2
139280	37.8	0.55	176	118	<0.5	<5	0.22	4	10	120	45	3.75	<1	0.19	<10	0.17	396	<2	0.01	4	637	99	2.50	8	1	6	<5	<0.01	<10	<10	11	<10	244	2
85143	12.7	2.45	20	36	<0.5	<5	5.70	41	26	215	735	5.38	<1	0.08	<10	2.90	2108	188	0.02	26	1123	1950	0.53	<5	14	264	<5	0.08	<10	<10	149	26	3238	3
85144	2.5	1.88	21	33	0.5	<5	6.33	3	23	213	335	4.66	<1	0.06	<10	1.83	1767	142	0.02	24	1153	15	0.46	<5	14	120	<5	0.12	<10	<10	142	<10	299	4
85145	2.9	2.33	28	37	<0.5	<5	6.90	4	30	235	407	5.28	<1	0.05	<10	2.24	2125	86	0.01	30	1265	167	0.27	<5	15	143	<5	0.11	<10	<10	169	<10	396	4
85146	2.9	1.46	18	48	0.5	<5	6.89	3	20	143	416	3.79	<1	0.08	<10	1.43	1717	44	0.02	20	1132	48	0.34	<5	6	147	<5	0.11	<10	<10	103	<10	261	4
85147	2.4	1.66	29	53	0.6	<5	6.78	2	26	187	414	4.13	<1	0.08	<10	1.63	1906	66	0.02	27	1317	22	0.47	<5	11	144	<5	0.14	<10	<10	143	<10	206	5
85148	1.8	1.48	33	87	0.6	<5	4.39	2	23	157	241	3.57	<1	0.12	<10	1.52	1554	81	0.02	22	1204	11	0.38	<5	6	117	<5	0.12	<10	<10	108	<10	209	4
85149	2.0	0.98	31	83	<0.5	<5	6.43	2	21	118	241	4.33	<1	0.18	<10	1.96	1949	136	0.01	21	1058	82	0.32	<5	16	350	<5	0.03	<10	<10	78	<10	235	2
85150	1.9	1.66	20	112	0.6	<5	4.94	3	25	152	286	4.39	<1	0.07	<10	1.77	1536	66	0.02	25	1265	12	0.43	<5	9	143	<5	0.13	<10	<10	116	<10	254	4
85151	<0.2	1.03	<5	259	0.8	<5	0.75	<1	9	107	9	2.20	<1	0.50	<10	0.65	662	4	0.07	6	711	6	0.01	<5	3	58	<5	0.13	<10	<10	44	<10	62	2
85152	2.1	1.52	19	39	0.6	<5	3.91	3	23	180	307	3.50	<1	0.06	<10	1.68	1204	69	0.03	21	1049	10	0.27	<5	5	88	<5	0.14	<10	<10	100	<10	333	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2768RP

Date : Aug-27-08

Ascot resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 14

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139270	59.9	0.51	190	154	<0.5	<5	0.31	8	7	59	58	4.32	<1	0.19	<10	0.14	211	7	0.01	2	687	301	2.48	8	2	12	<5	<0.01	<10	<10	12	<10	711	2
139271	24.6	0.94	114	215	<0.5	<5	0.19	4	8	42	32	4.28	<1	0.21	<10	0.36	381	3	0.01	1	969	333	1.80	5	2	7	<5	<0.01	<10	<10	17	<10	376	2
139272	8.1	0.48	524	121	<0.5	<5	0.38	12	7	79	26	3.93	<1	0.20	<10	0.12	276	<2	0.01	3	680	167	2.47	<5	1	12	<5	<0.01	<10	<10	7	<10	199	2
139273	>200.0	0.34	408	73	<0.5	<5	1.86	53	4	118	165	4.15	5	0.14	<10	0.10	329	3	0.01	2	400	4984	3.90	101	1	52	<5	<0.01	<10	<10	6	85	7540	2
139274	46.4	0.52	342	57	<0.5	5	0.17	25	10	97	120	7.78	1	0.17	<10	0.16	180	3	0.01	2	849	555	>5.00	13	1	5	<5	<0.01	<10	11	11	25	2314	3
139275	22.7	0.54	242	69	<0.5	5	0.27	12	9	94	80	6.91	1	0.16	<10	0.19	208	3	0.01	1	758	276	>5.00	7	1	6	<5	<0.01	<10	10	11	11	1049	3
139276	12.0	0.66	192	101	<0.5	<5	0.20	8	7	87	76	5.21	<1	0.18	<10	0.21	294	<2	0.01	2	699	248	2.63	5	1	5	<5	0.01	<10	<10	14	<10	676	2
139277	42.1	0.35	330	96	<0.5	<5	0.03	8	4	110	55	3.53	<1	0.16	<10	0.07	176	3	0.01	2	526	247	0.60	11	1	2	<5	<0.01	<10	<10	8	<10	247	2
139278	20.5	0.28	542	135	<0.5	<5	<0.01	12	2	68	14	3.74	1	0.23	<10	0.02	18	<2	0.01	1	767	217	0.55	10	1	3	<5	0.01	<10	<10	5	<10	203	2
139279	7.7	1.66	151	125	<0.5	<5	0.77	6	17	50	58	5.58	<1	0.25	<10	0.81	967	<2	0.01	5	930	113	2.73	<5	2	29	<5	<0.01	<10	<10	38	<10	422	2
139280	37.8	0.61	184	115	<0.5	<5	0.24	4	11	110	52	4.04	<1	0.20	<10	0.18	411	<2	0.01	5	680	105	2.48	8	1	6	<5	<0.01	<10	<10	11	<10	237	2
85143	13.2	2.85	22	36	<0.5	<5	6.33	40	27	218	795	5.93	<1	0.09	<10	3.02	2189	193	0.02	26	1195	1990	0.51	<5	14	294	<5	0.07	<10	<10	152	37	3176	3
85144	2.9	2.20	23	34	<0.5	<5	6.96	3	24	224	381	5.08	<1	0.06	<10	2.11	1865	154	0.02	25	1262	11	0.46	<5	14	135	<5	0.12	<10	<10	150	<10	300	4
85145	3.2	2.75	29	37	<0.5	<5	7.66	4	31	249	463	5.83	<1	0.06	<10	2.48	2252	87	0.01	31	1387	173	0.28	<5	15	161	<5	0.11	<10	<10	180	<10	405	4
85146	3.4	1.69	22	53	<0.5	<5	7.59	4	22	153	460	4.16	<1	0.10	<10	1.56	1835	44	0.02	22	1198	50	0.37	<5	7	161	<5	0.11	<10	<10	111	<10	268	4
85147	2.7	1.96	32	55	<0.5	<5	7.58	2	27	196	469	4.57	<1	0.10	<10	1.82	1999	65	0.02	28	1369	21	0.49	<5	11	160	<5	0.14	<10	<10	150	<10	205	4
85148	1.8	1.71	34	91	<0.5	<5	4.82	2	23	156	255	3.90	<1	0.13	<10	1.66	1574	84	0.03	22	1269	9	0.38	<5	6	129	<5	0.12	<10	<10	111	<10	201	4
85149	2.2	1.07	30	80	<0.5	<5	7.02	2	20	112	255	4.70	<1	0.19	<10	2.12	1950	132	0.01	21	1108	80	0.30	<5	17	380	<5	0.03	<10	<10	76	<10	220	2
85150	<0.2	1.12	<5	254	<0.5	<5	0.71	<1	9	94	10	2.20	<1	0.52	<10	0.68	647	4	0.08	6	762	4	0.01	<5	3	61	<5	0.13	<10	<10	43	<10	57	2
85151	2.0	1.89	20	119	<0.5	<5	5.24	3	26	156	312	4.64	<1	0.08	<10	2.00	1571	64	0.02	26	1277	11	0.41	<5	9	157	<5	0.12	<10	<10	121	<10	251	3
85152	2.3	1.75	20	39	<0.5	<5	4.11	3	23	181	320	3.69	<1	0.07	<10	1.90	1232	74	0.03	22	1163	8	0.27	<5	5	96	<5	0.14	<10	<10	102	<10	316	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2819-RA1

Company: **Ascot Resources Ltd**
 Project: **Dilworth/PO#shipment16**
 Attn: **Sue Deane**

Aug-12-08

We hereby certify the following assay of 22 core samples submitted Aug-08-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne	Pb %	Zn %
85406	3.47	3.05	181.6		2.56	4.56
85407	5.76		>200	237.6	7.30	11.2
85408	2.39		160.7			
85409	2.09		181.2			
85410	3.86		112.2			
85411	0.55		14.7			
85412	0.27		41.9			
85413	0.35		6.3			
85414	0.47		6.6			
85415	0.26	0.25	6.2			
85416	0.33		16.1			
85417	0.36		8.2			
85418	0.30		20.0			
85419	0.38		8.5			
85420	0.54		35.9			
85421	0.02		1.2			
85422	0.03		3.4			
85423	0.24		171.6			
85424	0.66		8.8			
85425	1.28	1.44	>200	218.5		
85426	0.02		3.5			
85427	3.77		>200	257.8		0.98
*0218	0.92					
*CCu-1c				129.2	0.33	3.92
*BLANK	<0.01			<0.1	<0.01	<0.01

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2819-RA2

Company: **Ascot Resources Ltd**
 Project: **Dilworth/PO#shipment16**
 Attn: **Sue Deane**

Aug-12-08

We hereby certify the following assay of 22 core samples submitted Aug-08-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne	Pb %	Zn %
85428	1.83	1.88	>200	296.8		
85429	1.33		151.5			
85430	0.28		8.7			
85431	0.09		2.1			
85432	0.14		4.3			
85433	0.38		22.7			
85434	0.14		5.6			
85435	0.05		2.4			
85436	0.07		2.3			
85437	0.04	0.02	2.1			
85438	0.02		2.4			
85439	0.05		0.7			
85440	0.06		2.0			
85441	0.06		1.0			
85442	0.02		0.9			
85443	0.02		1.1			
85444	2.02		87.4			
85445	1.83		87.0			
85446	2.79		58.7			
85447	2.92	3.12	86.3			0.99
85448	10.48		>200	199.9	4.54	8.40
85449	1.08		>200	574.2		
*0218	0.92					
*CCu-1c				129.2	0.33	3.92
*BLANK	<0.01			<0.1	<0.01	<0.01

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2819-RA3

Company: **Ascot Resources Ltd**
 Project: **Dilworth/PO#shipment16**
 Attn: **Sue Deane**

Aug-12-08

We hereby certify the following assay of 22 core samples submitted Aug-08-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
85450	<0.01	0.01	<0.2	
85451	3.29		>200	200.2
85452	0.52		98.6	
85453	1.04		139.4	
85454	0.57		20.5	
85455	0.37		6.2	
85456	0.29		26.5	
85457	0.10		3.4	
85458	0.25		6.2	
85459	0.21	0.21	11.8	
85460	0.32		8.0	
85461	0.26		6.5	
85462	0.16		7.4	
85463	0.11		8.1	
85464	0.04		2.5	
85465	0.02		2.9	
85466	0.25		4.0	
85467	0.02		1.7	
85468	0.10		0.9	
85469	0.10	0.12	1.1	
85470	0.18		5.0	
85471	0.02		1.8	
*0218	0.94			
*CCu-1c				129.2
*BLANK	<0.01			<0.1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2819-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment16**
Attn: **Sue Deane**

Aug-12-08

We *hereby certify* the following assay of 22 core samples submitted Aug-08-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
85472	0.01	0.04	3.5
85473	<0.01		1.4
85474	0.08		1.8
85475	5.94		2.7
85476	0.12		5.3
85477	0.13		3.8
85478	0.02		1.9
85479	0.02		2.0
85480	0.04		25.1
85481	0.05	0.06	10.0
85482	0.02		20.6
85483	0.02		8.8
*0218	0.91		
*BLANK	<0.01		

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2819RJ**

Date : Aug-12-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment16

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
85406	181.6	0.20	974	43	<0.5	<5	0.51	663	4	248	717	4.92	40	0.06	13	0.07	571	3	0.01	5	192	>10000	>5.00	103	<1	13	<5	<0.01	<10	<10	4	477	>10000	2
85407	>200.0	0.44	291	27	<0.5	<5	0.87	1389	5	137	2369	7.80	109	0.04	<10	0.26	1128	2	0.01	2	254	>10000	>5.00	140	<1	17	<5	<0.01	<10	<10	10	1185	>10000	3
85408	160.7	0.07	126	13	<0.5	<5	2.30	19	1	336	259	1.64	3	0.02	<10	0.03	4029	7	0.01	8	37	976	1.53	28	1	75	<5	<0.01	<10	11	<1	17	2344	1
85409	181.2	0.06	305	17	<0.5	<5	1.17	22	1	254	144	2.55	3	0.02	<10	0.02	2896	3	0.01	6	45	772	2.66	28	<1	43	<5	<0.01	<10	<10	<1	18	2467	1
85410	112.2	0.12	3467	43	<0.5	<5	0.33	90	4	276	571	8.00	2	0.08	14	0.02	220	4	0.01	6	217	1659	>5.00	84	<1	5	<5	<0.01	<10	<10	2	27	3549	3
85411	14.7	0.72	515	91	<0.5	<5	0.61	12	11	129	17	4.42	<1	0.28	<10	0.20	537	<2	0.01	4	683	88	4.12	6	1	21	<5	<0.01	<10	<10	12	<10	359	2
85412	41.9	1.18	288	111	<0.5	<5	0.85	8	13	191	22	4.25	<1	0.47	<10	0.28	576	2	0.02	7	982	202	3.39	5	2	38	<5	<0.01	<10	<10	21	<10	453	3
85413	6.3	0.85	254	123	<0.5	<5	0.72	5	13	72	14	4.49	<1	0.27	<10	0.28	584	<2	0.01	4	836	42	3.88	<5	2	44	<5	<0.01	<10	<10	13	<10	125	2
85414	6.6	1.27	318	120	<0.5	<5	0.66	7	13	142	28	4.49	<1	0.44	<10	0.37	621	2	0.02	6	1131	50	3.39	<5	2	33	<5	<0.01	<10	<10	20	<10	265	3
85415	6.2	0.79	337	103	<0.5	<5	1.63	7	13	54	16	4.97	<1	0.28	<10	0.27	769	<2	0.01	5	577	44	4.82	<5	2	58	<5	<0.01	<10	<10	12	<10	95	2
85416	16.1	1.09	324	134	<0.5	<5	1.20	8	13	93	11	4.40	<1	0.39	<10	0.35	733	<2	0.02	3	892	95	3.65	<5	2	45	<5	0.01	<10	<10	21	<10	342	3
85417	8.2	1.13	268	192	<0.5	<5	0.76	6	12	69	13	4.05	<1	0.32	<10	0.42	781	<2	0.01	2	916	55	2.67	<5	2	31	<5	0.03	<10	<10	24	<10	168	3
85418	20.0	1.12	287	149	<0.5	<5	0.76	6	13	98	15	4.32	<1	0.37	<10	0.40	974	2	0.01	3	890	81	3.29	<5	2	31	<5	0.04	<10	<10	24	<10	152	3
85419	8.5	0.97	204	200	<0.5	<5	1.26	4	11	67	18	3.51	<1	0.30	<10	0.34	1293	<2	0.01	2	1006	28	2.35	<5	2	45	<5	0.03	<10	<10	19	<10	77	2
85420	35.9	0.62	340	81	<0.5	<5	1.52	7	13	137	19	4.88	<1	0.40	<10	0.08	1178	2	0.01	4	918	91	>5.00	6	2	48	<5	0.03	<10	<10	14	<10	89	3
85421	1.2	2.03	20	228	0.7	<5	2.41	<1	19	27	12	4.98	<1	0.33	<10	0.99	1974	<2	0.02	1	1395	19	1.54	<5	3	67	<5	0.08	<10	<10	39	<10	122	3
85422	3.4	1.26	107	149	<0.5	<5	3.45	2	19	67	14	4.92	<1	0.33	<10	0.52	1708	<2	0.02	2	1443	23	3.56	<5	3	95	<5	0.04	<10	<10	28	<10	73	2
85423	171.6	0.95	74	205	<0.5	<5	1.38	1	13	78	35	3.80	<1	0.31	<10	0.28	827	14	0.03	3	988	24	2.52	6	2	49	<5	0.03	<10	<10	30	<10	67	3
85424	8.8	0.87	74	177	<0.5	<5	3.79	1	12	119	16	3.68	<1	0.38	<10	0.20	994	63	0.03	3	824	27	3.06	<5	3	124	<5	0.03	<10	<10	24	<10	56	3
85425	>200.0	0.89	1795	100	<0.5	50	4.63	39	60	22	2247	3.26	1	0.09	<10	0.25	945	117	0.05	24	822	418	0.72	304	2	144	<5	0.04	<10	<10	22	15	321	7
85426	3.5	1.84	106	222	<0.5	<5	3.08	1	16	34	74	4.71	<1	0.27	<10	0.94	2592	<2	0.02	3	915	14	1.25	<5	3	226	<5	<0.01	<10	<10	31	<10	107	2
85427	>200.0	0.10	412	32	<0.5	<5	1.22	103	3	393	966	4.16	11	0.04	<10	0.02	928	6	0.01	9	134	8376	4.96	104	<1	31	<5	<0.01	<10	<10	1	84	>10000	2
85428	>200.0	0.10	554	39	<0.5	<5	4.08	23	3	122	71	3.66	2	0.07	<10	0.02	793	6	0.01	2	156	1009	4.26	18	<1	100	<5	<0.01	<10	<10	2	19	2031	1
85429	151.5	0.37	582	112	<0.5	<5	1.97	13	7	96	34	4.15	<1	0.22	<10	0.06	405	5	0.01	1	588	339	4.71	8	1	54	<5	<0.01	<10	<10	7	<10	382	2
85430	8.7	1.13	237	148	<0.5	<5	0.96	5	14	80	10	4.87	<1	0.30	10	0.33	654	<2	0.02	3	996	66	3.41	<5	2	38	<5	0.01	<10	<10	25	<10	194	3
85431	2.1	1.65	137	169	<0.5	<5	2.10	2	16	50	11	5.36	<1	0.26	11	0.56	1298	<2	0.02	2	1131	14	2.15	<5	3	65	<5	0.04	<10	<10	39	<10	91	4
85432	4.3	1.11	167	134	<0.5	<5	2.97	3	15	64	9	5.31	<1	0.25	<10	0.38	1144	2	0.01	2	919	27	3.85	<5	2	104	<5	0.02	<10	<10	25	<10	77	3
85433	22.7	0.36	111	165	<0.5	<5	7.52	6	9	57	12	3.40	1	0.25	<10	0.07	1006	5	0.01	1	676	203	3.99	<5	3	229	<5	0.01	<10	<10	7	<10	654	2
85434	5.6	0.61	162	161	<0.5	<5	4.11	3	12	58	8	3.63	<1	0.28	<10	0.19	991	<2	0.01	2	757	30	3.64	<5	3	125	<5	0.03	<10	<10	11	<10	70	2
85435	2.4	0.82	54	123	<0.5	<5	1.84	1	13	58	13	4.07	<1	0.28	<10	0.33	859	2	0.01	2	952	20	3.68	<5	2	56	<5	0.02	<10	<10	16	<10	85	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2819RJ**

Date : Aug-12-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment16

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
85436	2.3	0.80	79	120	<0.5	<5	3.08	1	14	52	13	4.48	<1	0.26	<10	0.30	1283	<2	0.01	2	973	25	4.30	<5	2	106	<5	0.03	<10	<10	15	<10	73	3
85437	2.1	1.57	52	162	<0.5	<5	3.36	<1	14	36	17	4.17	<1	0.19	10	0.85	2236	<2	0.02	3	652	12	1.29	<5	2	83	<5	0.02	<10	<10	32	<10	76	2
85438	2.4	1.60	33	501	<0.5	<5	0.57	<1	14	42	30	4.77	<1	0.20	13	0.76	1683	<2	0.02	3	859	19	0.56	<5	3	15	<5	<0.01	<10	<10	39	<10	189	2
85439	0.7	1.95	32	184	<0.5	<5	1.22	<1	17	29	19	5.16	<1	0.23	15	0.99	1639	<2	0.02	2	1073	11	1.66	<5	3	39	<5	0.01	<10	<10	44	<10	95	3
85440	2.0	1.79	33	200	<0.5	<5	3.93	<1	14	33	22	4.34	<1	0.21	13	0.93	1953	<2	0.02	2	971	9	0.93	<5	3	96	<5	0.01	<10	<10	40	<10	75	2
85441	1.0	1.72	33	129	<0.5	<5	2.61	<1	14	25	18	4.36	<1	0.23	12	0.90	1807	<2	0.02	2	906	9	1.28	<5	3	61	<5	0.02	<10	<10	40	<10	72	2
85442	0.9	1.72	43	125	<0.5	<5	2.89	<1	14	34	16	4.53	<1	0.22	10	0.87	1963	<2	0.02	2	953	10	1.44	<5	3	65	<5	0.02	<10	<10	40	<10	72	2
85443	1.1	1.57	19	145	<0.5	<5	4.18	<1	13	32	12	3.72	<1	0.23	11	0.80	1954	<2	0.02	1	1794	12	1.11	<5	3	111	<5	0.04	<10	<10	26	<10	70	3
85444	87.4	0.17	368	74	<0.5	<5	1.09	66	4	120	173	4.70	8	0.10	<10	0.02	523	<2	0.01	2	514	3034	4.08	42	<1	15	<5	<0.01	<10	<10	4	57	7163	2
85445	87.0	0.29	502	84	<0.5	<5	0.87	21	8	110	65	5.23	2	0.16	<10	0.04	320	8	0.01	1	569	805	>5.00	21	1	23	<5	<0.01	<10	<10	6	16	1973	2
85446	58.7	0.30	734	70	<0.5	<5	0.61	27	8	123	74	6.41	2	0.15	<10	0.06	331	3	0.01	2	611	750	>5.00	29	1	14	<5	<0.01	<10	<10	7	16	2027	2
85447	86.3	0.25	1432	50	<0.5	<5	3.80	119	5	119	407	5.02	10	0.07	<10	0.10	3620	4	0.01	1	314	4779	>5.00	54	1	73	<5	<0.01	<10	<10	6	84	>10000	2
85448	>200.0	0.58	295	30	<0.5	<5	0.49	913	6	128	2152	8.67	76	0.05	<10	0.36	1196	<2	0.01	1	248	>10000	>5.00	111	<1	12	<5	<0.01	<10	<10	14	832	>10000	3
85449	>200.0	0.04	306	17	<0.5	<5	5.50	26	1	148	162	1.91	3	0.02	<10	0.01	8579	3	0.01	2	32	1318	2.25	80	<1	153	<5	<0.01	<10	37	<1	30	3849	<1
85450	<0.2	1.10	<5	284	0.8	<5	0.55	<1	9	135	<1	2.38	<1	0.53	<10	0.65	682	<2	0.08	6	789	13	0.01	<5	3	57	5	0.14	<10	<10	43	<10	60	2
85451	>200.0	0.15	794	84	<0.5	<5	2.39	40	3	127	68	4.78	3	0.10	<10	0.02	504	4	0.01	1	204	1517	>5.00	33	<1	112	<5	<0.01	<10	<10	2	31	3949	2
85452	98.6	0.24	235	145	<0.5	<5	3.07	12	4	137	24	1.90	1	0.14	<10	0.04	669	<2	0.01	3	262	376	1.96	9	1	105	<5	<0.01	<10	<10	4	<10	1261	1
85453	139.4	0.40	684	98	<0.5	<5	1.79	24	9	117	30	4.07	1	0.23	<10	0.07	490	4	0.01	2	651	540	4.50	11	1	61	<5	<0.01	<10	<10	7	14	1800	2
85454	20.5	0.91	396	123	<0.5	<5	5.67	9	11	44	12	4.83	<1	0.24	<10	0.35	1916	<2	0.01	4	586	157	4.38	<5	2	200	<5	<0.01	<10	<10	15	<10	409	2
85455	6.2	1.25	230	160	<0.5	<5	2.75	4	13	46	9	4.69	<1	0.26	<10	0.53	1405	<2	0.01	2	766	39	3.01	<5	2	108	<5	0.01	<10	<10	21	<10	118	2
85456	26.5	1.39	200	189	<0.5	<5	2.65	5	11	45	12	4.40	<1	0.24	<10	0.62	1807	<2	0.01	1	1062	101	2.11	<5	2	86	<5	0.01	<10	<10	26	<10	237	3
85457	3.4	1.60	156	220	<0.5	<5	1.18	3	12	54	18	4.21	<1	0.27	<10	0.68	1272	<2	0.02	1	1183	19	1.25	<5	2	45	<5	0.01	<10	<10	34	<10	96	4
85458	6.2	1.00	293	169	<0.5	<5	0.83	6	14	50	12	4.47	<1	0.27	<10	0.34	729	<2	0.01	2	1332	36	3.36	<5	2	31	<5	0.02	<10	<10	22	<10	84	4
85459	11.8	0.78	205	165	<0.5	<5	1.58	4	10	74	7	3.79	<1	0.27	<10	0.25	844	2	0.01	1	1029	32	3.05	<5	2	60	<5	0.01	<10	<10	15	<10	109	3
85460	8.0	1.11	313	163	<0.5	<5	1.03	6	13	42	16	4.35	<1	0.25	<10	0.45	831	<2	0.01	3	541	43	2.66	<5	2	32	<5	0.02	<10	<10	18	<10	128	2
85461	6.5	0.94	189	185	<0.5	<5	1.16	4	9	77	17	3.24	<1	0.25	<10	0.36	821	<2	0.01	2	740	51	1.88	<5	1	51	<5	0.01	<10	<10	17	<10	93	2
85462	7.4	0.90	223	153	<0.5	<5	1.07	4	13	49	10	4.39	<1	0.28	<10	0.33	628	2	0.01	2	942	33	3.52	<5	2	48	<5	0.04	<10	<10	18	<10	66	3
85463	8.1	0.56	217	115	<0.5	<5	4.78	4	11	62	7	4.57	<1	0.27	<10	0.16	737	<2	0.01	1	726	34	4.78	<5	2	153	<5	0.03	<10	<10	12	<10	36	3
85464	2.5	1.33	67	144	0.5	<5	1.16	1	19	26	10	5.17	<1	0.29	<10	0.61	1088	<2	0.01	1	1202	23	3.55	<5	3	42	<5	0.07	<10	<10	27	<10	96	3
85465	2.9	1.76	144	94	<0.5	<5	1.40	2	21	41	23	7.52	<1	0.25	10	0.73	1705	<2	0.01	<1	1192	23	4.95	<5	2	39	<5	0.02	<10	<10	48	<10	110	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2819RJ**

Date : Aug-12-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment16

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
85466	4.0	1.66	84	102	<0.5	<5	1.85	2	19	35	19	6.45	<1	0.27	14	0.66	1755	2	0.01	1	1664	33	3.72	<5	3	61	<5	0.01	<10	<10	53	<10	127	3
85467	1.7	2.54	65	165	<0.5	<5	0.94	1	20	25	32	7.51	<1	0.23	12	1.07	2294	<2	0.01	<1	1581	66	2.31	<5	3	33	<5	0.01	<10	<10	78	<10	215	3
85468	0.9	1.87	40	245	<0.5	<5	0.40	1	14	23	11	5.24	<1	0.24	14	0.83	1629	<2	0.01	<1	1002	46	1.26	<5	3	20	<5	<0.01	<10	<10	53	<10	188	2
85469	1.1	0.96	64	196	<0.5	<5	1.08	1	14	54	9	3.90	<1	0.30	12	0.36	1063	2	0.01	2	1075	26	2.43	<5	2	77	<5	<0.01	<10	<10	24	<10	64	2
85470	5.0	0.64	150	155	<0.5	<5	0.81	3	12	58	7	3.99	<1	0.28	11	0.20	681	4	0.01	2	777	38	3.44	<5	1	46	<5	<0.01	<10	<10	14	<10	64	2
85471	1.8	1.10	62	276	<0.5	<5	0.28	1	14	40	26	4.57	<1	0.24	17	0.26	827	<2	0.02	3	1123	20	0.93	<5	3	12	<5	<0.01	<10	<10	24	<10	100	2
85472	3.5	1.33	38	116	<0.5	<5	0.45	1	11	31	19	3.77	1	0.17	14	0.59	1067	<2	0.02	4	977	10	0.97	5	2	18	<5	<0.01	<10	<10	33	<10	78	3
85473	1.4	1.67	38	156	<0.5	<5	0.32	1	14	25	22	4.12	1	0.19	15	0.81	1331	<2	0.01	5	829	5	0.73	<5	2	23	<5	<0.01	<10	<10	34	<10	90	3
85474	1.8	1.18	57	136	<0.5	<5	0.42	1	11	36	17	3.82	1	0.21	14	0.52	941	<2	0.02	4	862	9	1.79	<5	2	19	<5	<0.01	<10	<10	30	<10	74	3
85475	2.7	1.96	585	271	0.8	180	9.52	2	48	141	468	6.87	12	0.22	18	0.41	1140	109	0.06	72	831	77	2.13	5	4	117	8	0.17	<10	<10	59	22	89	25
85476	5.3	0.95	96	142	<0.5	<5	0.18	1	10	67	24	3.25	1	0.16	13	0.45	817	3	0.01	4	580	27	0.84	5	1	10	<5	<0.01	<10	<10	19	<10	104	2
85477	3.8	1.51	42	151	<0.5	<5	0.59	1	12	36	20	3.55	1	0.20	11	0.86	1220	<2	0.02	4	920	21	0.84	<5	2	26	<5	0.01	<10	<10	30	<10	108	3
85478	1.9	1.71	37	183	<0.5	<5	2.01	1	13	30	19	3.75	<1	0.20	12	1.04	1870	<2	0.02	3	893	11	0.74	<5	2	83	<5	0.02	<10	<10	35	<10	80	3
85479	2.0	1.92	18	125	<0.5	<5	1.64	1	14	24	17	3.99	1	0.18	<10	1.16	1942	<2	0.02	3	969	9	0.47	<5	3	57	<5	0.04	<10	<10	41	<10	105	3
85480	25.1	1.55	30	119	<0.5	<5	3.09	2	16	24	20	3.87	<1	0.18	<10	0.91	2178	<2	0.01	4	914	43	1.17	6	2	110	<5	0.05	<10	<10	37	<10	290	3
85481	10.0	1.42	88	112	<0.5	<5	1.20	1	19	21	37	4.94	1	0.20	10	0.74	1608	<2	0.01	6	1210	31	2.62	5	2	54	<5	0.04	<10	<10	33	<10	93	4
85482	20.6	1.74	29	134	<0.5	<5	0.63	2	19	23	42	4.78	1	0.21	10	0.81	1741	<2	0.02	6	1120	84	1.35	<5	2	30	<5	0.02	<10	<10	39	<10	172	3
85483	8.8	1.73	77	143	<0.5	<5	0.66	1	17	21	35	4.18	1	0.21	<10	0.81	1914	<2	0.02	6	1141	11	0.68	<5	2	36	<5	0.02	<10	<10	37	<10	90	3
Blank-Inhouse	17.9	1.41	245	242	0.8	<5	2.66	56	22	82	328	4.38	1	0.32	13	0.61	891	3	0.03	11	722	4682	0.81	14	4	105	<5	0.07	<10	<10	85	<10	2375	7

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St.

Vancouver, B.C.

V5X 4R6

Tel: (604) 327-3436

Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2820-RA1

Company: **Ascot Resources Ltd**
Project: Dilworth/PO#shipment 16
Attn: Sue Deane

Aug-22-08

We hereby certify the following assay of 22 core samples submitted Aug-08-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
85365	0.02	0.03	2.7
85366	0.05		3.6
85367	0.06		2.0
85368	0.02		0.8
85369	0.02		0.7
85370	0.03		0.8
85371	0.13		1.8
85372	0.04		1.7
85373	1.95		5.9
85374	0.42	0.38	4.4
85375	0.46		0.1
85376	0.34		5.2
85377	0.15		2.4
85378	0.27		1.8
85379	0.06		0.2
85380	0.02		<0.1
85381	0.10		0.4
85382	7.89		3.8
85383	0.03		0.2
85384	0.04	0.03	0.3
85385	0.12		0.4
85386	0.15		1.9
*0218	0.92		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2820-RA2

Company: **Ascot Resources Ltd**
Project: Dilworth/PO#shipment 16
Attn: Sue Deane

Aug-22-08

We hereby certify the following assay of 22 core samples
submitted Aug-08-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
85387	0.22	0.23	1.3
85388	0.01		0.4
85389	<0.01		0.6
85390	0.03		0.9
85391	0.02		0.8
85392	0.11		0.5
85393	<0.01		0.6
85394	0.01		<0.1
85395	0.02		0.2
85396	0.08	0.08	1.4
85397	0.01		0.5
85398	0.02		0.4
85399	0.04		0.5
85400	0.01		<0.1
85401	<0.01		0.6
85402	0.05		2.0
85403	0.03		1.2
85404	0.05		2.7
85405	0.17		7.6
139324	0.10	0.09	10.2
139325	3.53		155
139326	0.03		3.7
*0218	0.94		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2820-RA3

Company: **Ascot Resources Ltd**
 Project: Dilworth/PO#shipment 16
 Attn: Sue Deane

Aug-22-08

We hereby certify the following assay of 22 core samples submitted Aug-08-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne	Pb %	Zn %
139327	0.40	0.40	6.1			
139328	0.37		12.7			
139329	0.43		14.5			
139330	0.63		22.8			
139331	0.58		27.5			
139332	1.32		9.2			
139333	11.82		42.4			
139334	11.15		78.2			
139335	2.04		12.2			
139336	1.59	1.55	39.1			2.55
139337	1.56		55.5			1.47
139338	0.58		28.8		1.86	
139339	0.99		17.7			
139340	0.78		13.9			
139341	1.21		66.7		4.94	4.98
Russ	3.58		19.7			
WDR0804	0.09		4.7			
WDR0805	0.01		<0.1			
WDR0806	0.02		<0.1			
WDR0807	0.02	0.01	<0.1			
WDR0808	0.04		1.2			
Ruby Showing grab	5.31		>200	3927	1.63	4.33
*0218	0.93					
*CCu-1c				129.7	0.35	3.97
*BLANK	<0.01			<0.1	<0.01	<0.01

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2820RJ**

Date : Aug-22-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment 16

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
85365	2.7	0.39	16	54	0.5	<5	5.35	<1	11	19	16	4.15	<1	0.28	<10	1.47	2801	<2	0.01	1	1119	22	0.54	<5	2	266	<5	<0.01	<10	<10	11	<10	98	2
85366	3.6	0.48	44	75	0.6	5	1.55	32	13	29	87	4.55	<1	0.35	<10	0.65	1596	2	0.01	2	1099	856	1.58	<5	2	69	<5	<0.01	<10	<10	22	29	3558	2
85367	2.0	0.45	46	61	0.6	<5	1.90	7	12	45	32	4.48	<1	0.30	10	0.67	1902	<2	0.01	2	1065	1332	1.22	<5	2	81	<5	<0.01	<10	<10	15	<10	917	2
85368	0.8	0.55	23	57	0.7	<5	1.93	1	15	29	29	4.16	<1	0.34	14	0.58	1560	3	0.01	2	1251	46	0.79	<5	3	94	<5	<0.01	<10	<10	15	<10	194	2
85369	0.7	0.52	16	77	0.6	<5	1.51	1	14	35	34	4.29	<1	0.38	14	0.60	1869	<2	0.01	2	1154	46	0.70	<5	4	69	<5	<0.01	<10	<10	16	<10	248	2
85370	0.8	0.53	15	63	0.6	<5	1.63	7	12	35	29	3.92	<1	0.38	14	0.64	1794	<2	0.01	2	1188	126	0.76	<5	3	66	<5	<0.01	<10	<10	16	<10	876	1
85371	1.8	0.45	42	64	0.5	<5	2.17	1	14	40	31	3.96	<1	0.35	10	0.56	1658	<2	0.01	2	1148	44	0.95	<5	3	90	<5	<0.01	<10	<10	16	<10	132	2
85372	1.7	1.49	13	189	0.5	<5	2.45	<1	11	63	184	2.92	<1	0.39	13	0.61	917	11	0.04	3	807	20	0.57	<5	2	122	<5	<0.01	<10	<10	29	<10	77	4
85373	5.9	0.51	141	74	<0.5	<5	3.89	3	5	74	16	2.32	<1	0.26	<10	0.14	1769	<2	0.01	1	733	167	2.21	<5	1	111	<5	<0.01	<10	<10	10	<10	101	1
85374	4.4	0.40	136	87	<0.5	<5	3.56	3	5	60	10	2.05	<1	0.24	<10	0.09	1639	<2	0.01	1	651	142	2.20	<5	1	105	<5	<0.01	<10	<10	8	<10	174	1
85375	<0.2	1.17	5500	21	<0.5	14	5.62	95	166	11	68	3.57	<1	0.05	11	0.21	705	12	0.07	30	1122	14	1.33	<5	2	92	<5	0.05	<10	<10	39	<10	90	9
85376	5.2	0.66	155	143	<0.5	<5	3.53	4	8	71	69	2.49	<1	0.33	<10	0.16	1400	2	0.01	2	783	241	2.14	<5	1	99	<5	<0.01	<10	<10	14	<10	243	1
85377	2.4	1.91	32	172	0.5	<5	4.14	2	14	20	122	4.27	<1	0.34	10	0.77	1967	7	0.01	1	1111	30	1.19	<5	4	136	<5	0.06	<10	<10	61	<10	192	3
85378	1.8	2.13	24	130	0.9	<5	1.99	1	22	27	135	4.57	<1	0.29	<10	0.88	1666	6	0.02	3	1152	24	1.00	<5	6	102	<5	0.16	<10	<10	88	<10	155	3
85379	0.2	2.28	9	92	0.7	<5	3.48	<1	17	14	42	4.70	<1	0.28	<10	1.09	1757	<2	0.03	2	1143	12	0.90	<5	5	161	<5	0.10	<10	<10	85	<10	94	3
85380	<0.2	1.82	10	131	0.8	<5	3.82	<1	15	19	30	3.80	<1	0.35	<10	0.66	1660	<2	0.04	1	1330	10	0.81	<5	5	171	<5	0.11	<10	<10	70	<10	75	3
85381	0.4	1.73	72	113	0.7	<5	3.72	1	11	10	13	3.89	<1	0.29	<10	0.78	1658	<2	0.02	<1	1307	17	0.78	<5	4	119	<5	0.10	<10	<10	57	<10	110	3
85382	3.8	1.62	867	138	0.7	<5	3.70	16	11	12	27	3.65	<1	0.41	<10	0.57	1791	<2	0.01	<1	1207	455	1.02	<5	3	104	<5	0.09	<10	<10	34	<10	115	2
85383	0.2	2.15	15	118	0.8	<5	3.38	1	11	13	14	3.78	<1	0.34	<10	0.84	1788	<2	0.04	<1	1258	25	0.46	<5	3	136	<5	0.10	<10	<10	53	<10	155	3
85384	0.3	2.19	13	113	0.8	<5	3.59	<1	12	16	22	3.89	<1	0.34	<10	0.86	1685	<2	0.05	<1	1248	21	0.55	<5	4	129	<5	0.12	<10	<10	58	<10	120	3
85385	0.4	2.11	56	199	1.0	<5	3.61	1	12	11	15	3.85	<1	0.45	<10	0.76	1896	<2	0.04	<1	1277	34	0.71	<5	4	107	<5	0.13	<10	<10	61	<10	119	3
85386	1.9	2.26	799	123	0.5	<5	7.86	14	13	12	66	5.59	<1	0.28	<10	0.98	3206	<2	0.02	1	893	77	2.59	5	3	177	<5	0.05	<10	<10	52	<10	187	3
85387	1.3	1.09	1644	130	0.6	<5	6.44	29	12	54	28	3.53	<1	0.60	<10	0.19	1576	<2	0.02	2	1125	51	3.40	19	2	194	<5	0.03	<10	<10	17	<10	165	2
85388	0.4	2.29	27	139	0.9	<5	3.28	1	11	27	19	4.13	<1	0.33	<10	0.89	2032	<2	0.06	<1	1321	40	0.73	<5	4	107	<5	0.11	<10	<10	76	<10	160	3
85389	0.6	2.06	44	127	0.7	<5	3.00	1	12	45	32	3.86	<1	0.38	<10	0.66	1607	2	0.06	1	1122	40	1.14	<5	3	112	<5	0.09	<10	<10	46	<10	129	3
85390	0.9	2.01	196	123	0.5	<5	2.26	3	12	21	60	4.40	<1	0.40	<10	0.63	1464	3	0.05	1	1161	29	1.64	<5	2	89	<5	0.04	<10	<10	39	<10	105	2
85391	0.8	2.38	40	137	0.6	<5	2.76	1	15	32	50	4.50	<1	0.36	10	0.71	1627	2	0.09	1	1202	45	1.42	<5	3	96	<5	0.05	<10	<10	56	<10	136	3
85392	0.5	2.24	58	120	0.6	<5	2.49	1	13	15	38	4.33	<1	0.44	<10	0.55	1346	4	0.06	1	1266	27	1.33	<5	3	71	<5	0.07	<10	<10	56	<10	102	2
85393	0.6	2.35	24	162	0.8	<5	2.75	<1	13	23	37	4.04	<1	0.40	<10	0.80	1355	2	0.10	1	1226	30	0.98	<5	4	87	<5	0.09	<10	<10	61	<10	114	3
85394	<0.2	2.28	14	269	0.8	<5	2.87	<1	16	11	56	4.65	<1	0.43	<10	0.95	1392	3	0.04	2	1345	18	0.93	<5	4	157	<5	0.01	<10	<10	74	<10	89	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2820RJ

Date : Aug-22-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment 16

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
85395	0.2	1.78	25	126	0.8	<5	1.36	<1	13	31	42	3.48	<1	0.51	<10	0.60	568	2	0.04	2	1258	24	1.29	<5	2	104	<5	<0.01	<10	<10	44	<10	84	2
85396	1.4	1.16	95	258	0.6	<5	3.93	1	5	54	15	3.06	<1	0.40	<10	0.33	1048	<2	0.01	1	735	14	1.07	<5	2	100	<5	<0.01	<10	<10	23	<10	32	2
85397	0.5	0.96	16	396	0.5	<5	4.22	<1	9	51	15	1.96	<1	0.47	12	0.40	1038	<2	0.03	2	941	19	0.27	<5	2	243	<5	<0.01	<10	<10	15	<10	76	3
85398	0.4	0.63	11	223	<0.5	<5	2.32	<1	8	53	22	1.92	<1	0.35	14	0.38	628	<2	0.03	3	876	18	0.24	<5	2	154	<5	<0.01	<10	<10	10	<10	52	3
85399	0.5	0.83	14	100	0.5	<5	5.37	<1	16	75	13	4.28	<1	0.53	17	1.36	2003	<2	0.04	11	1763	13	0.19	<5	5	317	<5	<0.01	<10	<10	15	<10	80	3
85400	<0.2	1.22	<5	268	0.9	<5	0.53	<1	9	143	<1	2.22	<1	0.61	10	0.57	642	<2	0.07	7	747	6	<0.01	<5	3	53	6	0.14	<10	<10	42	<10	58	2
85401	0.6	0.75	21	77	0.5	<5	4.73	<1	16	92	14	4.05	<1	0.46	13	1.23	1745	<2	0.03	12	1702	17	0.42	<5	4	251	<5	<0.01	<10	<10	14	<10	93	3
85402	2.0	0.62	83	87	<0.5	<5	3.05	2	12	42	33	4.71	<1	0.44	<10	0.85	2120	<2	0.03	2	1171	39	1.61	<5	3	146	<5	<0.01	<10	<10	16	<10	141	2
85403	1.2	0.81	39	87	0.5	<5	3.01	1	11	66	21	3.54	<1	0.59	<10	0.83	1847	<2	0.03	3	1178	33	0.94	<5	2	140	<5	<0.01	<10	<10	14	<10	94	2
85404	2.7	0.48	22	66	<0.5	<5	3.34	2	9	49	29	2.52	<1	0.39	<10	0.70	1624	<2	0.02	3	825	300	0.57	<5	2	162	<5	<0.01	<10	<10	9	<10	326	2
85405	7.6	0.56	346	72	<0.5	<5	4.58	29	16	97	125	6.04	<1	0.37	<10	0.53	2080	<2	0.01	4	809	1268	3.83	<5	2	120	<5	<0.01	<10	<10	21	24	2816	2
139324	10.2	0.69	164	195	<0.5	<5	0.13	3	4	178	10	3.36	<1	0.40	<10	0.08	186	28	0.03	4	815	126	0.97	6	1	7	<5	<0.01	<10	<10	13	<10	156	2
139325	155.5	1.42	80	382	<0.5	<5	0.03	10	3	662	45	3.22	5	0.84	<10	0.10	157	13	0.02	16	520	2169	0.60	24	2	7	<5	<0.01	<10	<10	19	12	1415	2
139326	3.7	0.82	42	194	<0.5	<5	0.10	<1	4	62	16	3.31	<1	0.38	<10	0.16	270	3	0.01	2	887	34	0.80	<5	1	4	<5	0.01	<10	<10	16	<10	48	2
139327	6.1	1.20	80	146	<0.5	<5	0.07	1	6	34	24	4.92	<1	0.23	<10	0.35	865	<2	0.01	2	667	85	0.42	<5	2	3	<5	<0.01	<10	<10	22	<10	127	2
139328	12.7	0.40	386	140	<0.5	<5	0.06	7	4	71	20	5.55	<1	0.20	<10	0.04	227	3	0.01	<1	665	95	0.88	11	1	5	<5	<0.01	<10	<10	9	<10	217	2
139329	14.5	0.26	482	125	<0.5	<5	0.01	8	2	80	15	3.36	2	0.19	<10	0.02	27	<2	0.01	1	348	131	0.89	33	<1	3	<5	<0.01	<10	<10	5	<10	133	1
139330	22.8	0.63	262	82	<0.5	<5	0.07	8	5	93	43	4.09	1	0.13	<10	0.20	232	3	0.01	1	564	196	1.59	21	1	2	<5	<0.01	<10	<10	13	<10	671	2
139331	27.5	0.60	158	61	<0.5	<5	0.26	4	6	126	32	2.85	<1	0.11	<10	0.19	391	<2	0.01	3	407	152	0.78	5	1	7	<5	<0.01	<10	<10	10	<10	324	1
139332	9.2	1.52	162	131	<0.5	<5	1.05	15	14	49	106	6.19	2	0.20	<10	0.60	2072	<2	0.01	2	1034	1854	0.89	<5	3	28	<5	<0.01	<10	<10	47	18	2153	2
139333	42.4	0.41	490	106	<0.5	<5	0.20	12	7	103	45	5.76	3	0.19	<10	0.10	620	<2	0.01	2	690	2290	1.05	<5	2	8	<5	<0.01	<10	<10	11	11	1271	2
139334	78.2	0.33	407	119	<0.5	<5	0.15	10	8	85	85	7.40	6	0.23	<10	0.03	628	<2	0.01	1	870	9961	1.02	14	2	7	<5	<0.01	<10	<10	14	14	1577	3
139335	12.2	0.58	96	113	<0.5	<5	0.41	64	8	138	367	3.25	2	0.21	<10	0.16	740	<2	0.01	4	514	1699	2.43	<5	1	13	<5	<0.01	<10	<10	9	73	9374	1
139336	39.1	0.65	177	32	<0.5	<5	0.44	242	12	97	1487	7.74	6	0.18	<10	0.23	1001	<2	0.01	1	565	5088	>5.00	5	1	10	<5	<0.01	<10	<10	13	241	>10000	3
139337	55.5	1.62	147	58	<0.5	<5	0.73	110	15	61	853	7.93	5	0.21	<10	0.85	1364	<2	0.01	2	775	4880	4.38	8	2	16	<5	0.01	<10	<10	51	117	>10000	3
139338	28.8	1.98	363	59	<0.5	<5	0.17	8	10	37	395	9.81	<1	0.82	<10	1.02	1431	19	0.02	<1	959	>10000	3.76	<5	5	7	<5	0.10	<10	<10	116	10	722	5
139339	17.7	2.65	765	31	<0.5	<5	0.21	56	15	57	143	11.67	<1	1.14	<10	1.41	1758	4	0.02	<1	936	7593	>5.00	<5	6	7	<5	0.09	<10	<10	107	63	6145	5
139340	13.9	2.62	588	45	<0.5	<5	0.21	60	13	58	165	11.63	<1	1.05	<10	1.53	2163	15	0.02	<1	811	2448	>5.00	<5	5	7	<5	0.08	<10	<10	95	63	7140	5
139341	66.7	0.98	802	69	<0.5	<5	3.16	378	8	37	3643	14.88	<1	0.24	<10	0.49	1756	4	0.01	<1	605	>10000	>5.00	13	2	42	<5	0.02	<10	<10	25	331	>10000	6
Russ	19.7	1.28	1376	28	<0.5	<5	0.17	53	31	80	338	12.09	<1	0.14	<10	0.72	1422	3	0.01	<1	779	6016	>5.00	<5	2	3	<5	0.04	<10	<10	58	35	4241	5

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment 16

Sample type:

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2820RJ

Date : Aug-22-08

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
WDR0804	4.7	0.89	46	73	<0.5	<5	0.38	22	8	31	246	5.85	<1	0.24	<10	0.31	331	<2	0.03	8	1364	3550	4.80	<5	2	15	<5	<0.01	<10	<10	14	22	2723	4
WDR0805	<0.2	1.13	9	122	0.9	<5	0.69	<1	18	55	16	4.82	<1	0.18	<10	0.55	562	<2	0.03	2	1193	142	2.98	<5	3	25	<5	0.17	<10	<10	25	<10	156	6
WDR0806	<0.2	0.65	11	202	<0.5	<5	0.49	<1	6	28	14	5.12	<1	0.28	15	0.09	140	<2	0.03	1	1944	171	1.48	<5	3	44	<5	<0.01	<10	<10	26	<10	184	4
WDR0807	<0.2	0.58	6	118	<0.5	<5	2.02	<1	10	43	13	4.16	<1	0.27	14	0.07	336	<2	0.04	4	2526	132	3.38	<5	4	121	<5	<0.01	<10	<10	11	<10	173	5
WDR0808	1.2	1.04	25	96	0.8	<5	1.18	11	13	42	109	5.31	<1	0.15	<10	0.59	625	<2	0.03	2	1292	1213	3.82	<5	2	27	<5	0.14	<10	<10	22	12	1434	5
Ruby Showing grab	>200.0	0.10	1367	13	<0.5	8	0.02	344	3	124	895	11.73	3	0.08	<10	0.01	160	<2	0.01	<1	381	>10000	>5.00	391	<1	8	<5	<0.01	<10	<10	4	419	>10000	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2821-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment 15**
Attn: **Sue Deane**

Aug-20-08

We hereby certify the following assay of 22 core samples submitted Aug-04-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
85232	<0.01	0.01	0.2
85233	0.03		0.6
85234	0.06		0.8
85235	0.04		1.0
85236	0.03		0.5
85237	0.06		0.6
85238	0.13		0.7
85239	0.04		0.2
85240	0.04		0.3
85241	0.02	0.02	0.2
85242	0.05		0.5
85243	0.03		0.3
85244	0.06		0.5
85245	0.03		<0.1
85246	0.05		0.1
85247	0.10		0.1
85248	0.04		0.9
85249	0.06		0.3
85250	<0.01		<0.1
85251	0.08	0.08	3.3
85252	0.11		0.9
85253	0.13		0.7
*0218	0.96		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2821-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment 15**
Attn: **Sue Deane**

Aug-20-08

We hereby certify the following assay of 22 core samples submitted Aug-04-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
85254	0.19	0.16	0.5
85255	0.10		1.2
85256	0.15		1.2
85257	0.04		0.4
85258	0.05		0.2
85259	0.01		0.5
85260	0.04		2.1
85261	0.05		0.3
85262	0.03		<0.1
85263	0.07	0.08	1.2
85264	0.05		0.4
85265	0.07		0.4
85266	0.05		0.7
85267	0.03		1.1
85268	0.04		4.9
85269	0.06		0.6
85270	0.01		0.3
85271	0.03		0.2
85272	0.02		0.4
85273	0.05	0.04	1.7
85274	0.03		0.7
85275	1.76		173
*0218	0.91		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2821-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment 15**
Attn: **Sue Deane**

Aug-20-08

We hereby certify the following assay of 22 core samples submitted Aug-04-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
85276	0.02	0.02	0.5
85277	0.06		0.9
85278	0.04		0.6
85279	0.06		0.6
85280	0.04		0.9
85281	0.05		0.8
85282	0.01		0.6
85283	<0.01		<0.1
85284	0.02		0.7
85285	0.07	0.05	1.5
85286	0.02		0.1
85287	0.04		0.7
85288	0.06		0.9
85289	0.08		1.9
85290	0.04		1.1
85291	0.09		1.5
85292	0.09		1.1
85293	0.12		1.0
85294	0.08		1.4
85295	0.04	0.06	1.4
85296	0.07		2.3
85297	0.10		2.8
*0218	0.87		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2821-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment 15**
Attn: **Sue Deane**

Aug-20-08

We hereby certify the following assay of 22 core samples submitted Aug-04-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
85298	0.28	0.29	5.4
85299	0.04		0.8
85300	<0.01		<0.1
85301	0.28		0.3
85302	0.01		0.1
85303	0.01		<0.1
85304	0.03		<0.1
85305	0.02		0.2
85306	0.02		0.2
85307	0.09	0.10	0.7
85308	0.13		1.3
85309	0.09		4.6
85310	0.09		1.5
85311	0.06		1.3
85312	0.11		2.8
85313	0.05		1.5
85314	0.09		0.3
85315	0.08		1.2
85316	0.04		1.3
85317	0.12	0.11	2.3
85318	0.18		2.7
85319	0.39		2.9
*0218	0.91		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2821-RA5

Company: **Ascot Resources Ltd**
 Project: **Dilworth/PO#shipment 15**
 Attn: **Sue Deane**

Aug-20-08

We hereby certify the following assay of 22 core samples submitted Aug-04-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
85320	0.27	0.23	2.1	
85321	0.13		0.9	
85322	0.11		0.9	
85323	0.15		1.2	
85324	0.14		1.4	
85325	0.09		>200	792.5
85326	0.10		1.3	
85327	0.20		1.7	
85328	0.20		1.0	
85329	0.10	0.10	1.0	
85330	0.14		0.5	
85331	0.26		0.9	
85332	0.65		3.6	
85333	1.31		2.7	
85334	0.04		0.7	
85335	0.10		0.9	
85336	0.03		1.2	
85337	0.27		2.0	
85338	0.06		0.5	
85339	0.06	0.04	1.3	
85340	0.03		0.8	
85341	0.02		0.9	
*0218	0.92			
*CCu-1c				131.6
*BLANK	<0.01			<0.1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2821-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO#shipment 15**
Attn: **Sue Deane**

Aug-20-08

We hereby certify the following assay of 22 core samples submitted Aug-04-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
85342	0.03	0.04	1.2
85343	0.01		0.7
85344	0.06		1.6
85345	0.27		1.7
85346	0.03		2.5
85347	0.07		4.7
85348	0.27		11.3
85349	0.25		2.1
85350	<0.01		<0.1
85351	0.34	0.35	5.0
85352	2.02		9.5
85353	0.32		4.6
85354	0.01		<0.1
85355	0.30		<0.1
85356	<0.01		<0.1
85357	<0.01		<0.1
85358	0.01		0.4
85359	0.01		0.3
85360	0.01		1.0
85361	0.50	0.56	6.0
85362	0.01		1.1
85363	0.01		0.8
*0218	0.95		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2821-RA7

Company: **Ascot Resources Ltd**
 Project: **Dilworth/PO#shipment 15**
 Attn: **Sue Deane**

Aug-20-08

We hereby certify the following assay of 22 core samples submitted Aug-04-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne	Pb %	Zn %
85364	0.01	0.02	2.0			
139281	8.21		126		1.16	1.18
139282	6.24		101		1.15	2.32
139283	7.96		127			2.29
139284	11.30		126		1.25	3.66
139285	2.67		168			
139286	4.34		176			
139287	0.56		47.9			
139288	0.19		12.2			
139289	1.73	1.61	>200	271.9		
139290	4.52		>200	659.1		
139291	0.89		23.0			
139292	4.13		>200	213.3		
139293	4.26		>200	243.7		
139294	2.53		>200	239.4		
139295	22.46		>200	1281.0		
139296	7.14		>200	319.2		
139297	4.52		>200	318.5		
139298	3.77		152			
139299	3.20	3.21	158			
139300	0.52		9.6			1.54
139301	0.45		9.7			
*0218	0.89					
*CCu-1c				129.2	0.35	3.97
*BLANK	<0.01			<0.1	<0.01	<0.01

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2821-RA8

Company: **Ascot Resources Ltd**
 Project: **Dilworth/PO#shipment 15**
 Attn: **Sue Deane**

Aug-20-08

We hereby certify the following assay of 22 core samples submitted Aug-04-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
139302	0.74	0.62	9.4	
139303	0.37		3.6	
139304	0.24		7.2	
139305	0.21		6.2	
139306	0.08		2.8	
139307	0.07		2.7	
139308	0.05		1.1	
139309	0.16		7.6	
139310	0.25		10.2	
139311	0.22	0.21	16.0	
139312	0.30		47.3	
139313	0.31		15.9	
139314	0.68		98.4	
139315	1.51		75.2	
139316	0.64		>200	203.8
139317	20.73		198	
139318	0.39		25.1	
139319	0.32		21.9	
139320	0.44		38.6	
139321	0.94	0.96	123	
139322	1.04		49.8	
139323	0.70		29.7	
*0218	0.92			
*CCu-1c				129.2
*BLANK	<0.01			<0.1

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2821RJ

Date : Aug-20-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment 15

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
85232	0.2	0.38	<5	304	<0.5	<5	2.67	<1	7	19	16	2.00	<1	0.33	10	0.59	1075	<2	0.03	3	766	18	0.49	<5	3	178	<5	<0.01	<10	<10	5	<10	50	5
85233	0.6	0.49	20	69	<0.5	<5	2.38	<1	11	83	46	2.97	<1	0.24	<10	0.57	1035	5	0.01	2	639	17	0.98	<5	3	133	<5	<0.01	<10	<10	14	<10	46	1
85234	0.8	0.45	47	63	<0.5	<5	2.49	1	14	60	41	2.88	<1	0.25	<10	0.42	1124	3	0.01	2	547	17	1.80	<5	2	121	<5	<0.01	<10	<10	11	<10	32	2
85235	1.0	0.42	27	81	<0.5	<5	2.42	<1	12	64	45	2.75	<1	0.32	<10	0.38	962	4	0.01	2	710	35	1.33	<5	3	135	<5	<0.01	<10	<10	8	<10	45	2
85236	0.5	0.78	24	82	<0.5	<5	2.71	<1	10	51	41	3.21	<1	0.27	<10	0.59	1407	2	0.01	2	705	18	1.02	<5	3	156	<5	<0.01	<10	<10	17	<10	51	2
85237	0.6	1.31	152	113	<0.5	<5	3.63	3	10	51	29	3.54	<1	0.24	<10	0.73	1397	2	0.01	1	808	18	0.65	<5	4	119	<5	<0.01	<10	<10	44	<10	101	2
85238	0.7	1.41	52	107	<0.5	<5	3.34	1	11	45	28	3.77	<1	0.27	<10	0.79	1324	2	0.02	1	872	12	0.68	<5	4	114	<5	<0.01	<10	<10	48	<10	72	2
85239	0.2	1.46	24	91	<0.5	<5	3.05	<1	11	55	23	4.13	<1	0.23	10	0.94	1317	2	0.02	1	883	19	0.39	<5	6	164	<5	<0.01	<10	<10	48	<10	101	2
85240	0.3	1.42	11	91	<0.5	<5	3.00	<1	10	49	14	3.80	<1	0.20	11	0.83	1170	2	0.03	2	861	7	0.16	<5	5	132	<5	<0.01	<10	<10	50	<10	84	2
85241	0.2	1.36	13	95	<0.5	<5	2.60	<1	9	72	9	3.72	<1	0.22	<10	0.84	1147	4	0.03	2	850	15	0.34	<5	5	127	<5	<0.01	<10	<10	44	<10	75	2
85242	0.5	1.21	32	111	<0.5	<5	2.48	1	11	50	20	3.73	<1	0.24	<10	0.70	1197	2	0.02	2	891	22	0.41	<5	5	131	<5	<0.01	<10	<10	29	<10	111	2
85243	0.3	1.13	18	74	<0.5	<5	4.37	<1	9	59	19	3.14	<1	0.20	<10	0.73	1511	4	0.02	1	798	16	0.38	<5	5	161	<5	<0.01	<10	<10	37	<10	54	2
85244	0.5	1.15	26	72	<0.5	<5	4.55	<1	9	43	76	3.22	<1	0.19	<10	0.60	1542	3	0.01	1	746	10	0.50	<5	3	143	<5	<0.01	<10	<10	43	<10	55	1
85245	<0.2	0.68	7	64	<0.5	<5	>15.00	<1	5	30	10	1.95	<1	0.11	<10	0.34	4210	2	0.01	1	480	2	0.18	<5	2	234	<5	<0.01	<10	<10	22	<10	26	1
85246	<0.2	1.27	33	73	<0.5	<5	3.42	1	9	47	14	3.55	<1	0.22	<10	0.74	1322	2	0.02	1	780	35	0.50	<5	4	99	<5	<0.01	<10	<10	42	<10	130	2
85247	<0.2	0.98	45	79	<0.5	<5	2.52	1	9	47	10	3.22	<1	0.26	<10	0.66	1107	4	0.02	1	770	15	0.49	<5	4	131	<5	<0.01	<10	<10	29	<10	55	2
85248	0.9	0.87	37	83	<0.5	<5	4.91	1	8	43	12	3.10	<1	0.25	<10	0.78	1829	2	0.02	2	724	18	0.43	<5	4	222	<5	<0.01	<10	<10	27	<10	70	2
85249	0.3	1.10	36	89	<0.5	<5	3.16	1	9	51	14	3.20	<1	0.26	<10	0.59	1348	3	0.01	1	727	24	0.56	<5	3	81	<5	<0.01	<10	<10	30	<10	91	2
85250	<0.2	0.99	<5	271	0.7	<5	0.54	<1	9	90	<1	2.21	<1	0.52	<10	0.64	628	<2	0.07	6	748	5	0.01	<5	2	47	<5	0.13	<10	<10	41	<10	57	2
85251	3.3	1.22	45	71	<0.5	<5	4.71	19	11	44	160	3.92	<1	0.21	<10	0.64	1691	4	0.01	1	793	938	1.19	<5	3	119	<5	<0.01	<10	<10	51	17	2081	2
85252	0.9	0.70	64	113	<0.5	<5	4.01	5	12	66	44	3.53	<1	0.29	<10	0.44	1563	3	0.01	3	765	95	0.68	<5	3	145	<5	<0.01	<10	<10	17	<10	520	1
85253	0.7	1.24	56	100	<0.5	<5	3.88	1	13	54	22	4.01	<1	0.29	<10	0.70	1516	4	0.01	2	699	17	0.74	<5	3	187	<5	<0.01	<10	<10	38	<10	63	2
85254	0.5	1.78	35	145	<0.5	<5	1.39	1	14	33	22	4.30	<1	0.34	<10	0.63	1189	3	0.01	3	513	17	0.37	<5	4	74	<5	<0.01	<10	<10	40	<10	127	2
85255	1.2	1.22	82	210	<0.5	<5	2.83	2	10	62	62	3.47	<1	0.37	<10	0.48	1165	4	0.01	2	823	96	0.85	<5	2	167	<5	<0.01	<10	<10	20	<10	223	2
85256	1.2	0.98	121	181	<0.5	<5	4.32	4	8	60	31	2.91	<1	0.30	<10	0.48	1489	3	0.01	2	656	55	1.32	<5	2	283	<5	<0.01	<10	<10	20	<10	296	1
85257	0.4	1.21	45	247	<0.5	<5	3.44	<1	8	75	22	3.02	<1	0.26	<10	0.57	1401	3	0.01	2	663	9	0.78	<5	3	134	<5	<0.01	<10	<10	33	<10	49	1
85258	0.2	1.13	49	410	<0.5	<5	2.35	1	8	67	12	2.99	<1	0.27	<10	0.49	1011	3	0.01	2	629	11	0.82	<5	3	102	<5	<0.01	<10	<10	27	<10	51	1
85259	0.5	0.76	21	434	<0.5	<5	3.44	1	9	58	14	3.28	<1	0.32	<10	0.70	1711	3	0.01	1	813	29	0.40	<5	4	284	<5	<0.01	<10	<10	14	<10	104	1
85260	2.1	0.78	29	98	<0.5	<5	3.99	5	7	55	55	3.15	<1	0.31	<10	0.64	1834	2	0.01	2	747	148	0.59	<5	4	276	<5	<0.01	<10	<10	13	<10	423	1
85261	0.3	1.14	67	91	<0.5	<5	1.80	1	8	85	7	2.99	<1	0.29	<10	0.52	1051	3	0.01	2	671	29	0.84	<5	2	82	<5	<0.01	<10	<10	25	<10	104	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2821RJ

Date : Aug-20-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment 15

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
85262	<0.2	1.65	40	97	<0.5	<5	1.69	<1	10	39	22	3.79	<1	0.34	10	0.87	1192	2	0.01	2	950	11	0.65	<5	4	78	<5	<0.01	<10	<10	40	<10	65	2
85263	1.2	1.21	86	86	<0.5	<5	1.78	2	9	72	13	3.32	<1	0.34	<10	0.56	1209	3	0.01	2	739	88	1.02	<5	2	102	<5	<0.01	<10	<10	25	<10	158	2
85264	0.4	1.02	35	132	<0.5	<5	3.98	2	7	54	25	3.01	<1	0.26	<10	0.53	1640	3	0.01	1	676	11	0.68	<5	3	162	<5	<0.01	<10	<10	28	<10	231	1
85265	0.4	1.23	71	209	<0.5	<5	1.45	1	10	59	16	3.71	<1	0.37	<10	0.54	1029	3	0.01	1	799	21	1.08	<5	3	74	<5	<0.01	<10	<10	26	<10	62	2
85266	0.7	0.96	61	130	<0.5	<5	2.26	1	9	51	33	3.42	<1	0.37	<10	0.44	1328	2	0.01	2	725	31	0.80	<5	3	91	<5	<0.01	<10	<10	21	<10	128	2
85267	1.1	0.88	38	99	<0.5	<5	3.30	2	8	41	33	2.69	<1	0.38	<10	0.42	1534	3	0.01	1	745	63	0.74	<5	2	207	<5	<0.01	<10	<10	13	<10	189	2
85268	4.9	0.62	21	116	<0.5	<5	3.61	31	7	22	80	3.14	<1	0.39	<10	0.53	1913	<2	0.01	1	800	2035	1.12	<5	2	274	<5	<0.01	<10	<10	16	31	3777	2
85269	0.6	1.18	76	88	<0.5	<5	3.81	3	8	40	19	3.22	<1	0.26	<10	0.61	1840	3	0.01	1	762	125	1.36	<5	2	147	<5	<0.01	<10	<10	32	<10	309	2
85270	0.3	1.33	34	93	<0.5	<5	3.39	<1	7	25	8	3.10	<1	0.31	<10	0.61	1719	<2	0.01	1	808	21	0.89	<5	2	160	<5	<0.01	<10	<10	36	<10	73	2
85271	0.2	1.24	20	116	<0.5	<5	3.39	<1	7	36	10	3.04	<1	0.32	<10	0.59	1671	2	0.02	1	779	12	0.65	<5	2	257	<5	<0.01	<10	<10	33	<10	55	2
85272	0.4	0.55	31	401	<0.5	<5	2.48	<1	9	41	15	3.38	<1	0.37	<10	0.66	1813	2	0.01	1	799	18	0.93	<5	3	157	<5	<0.01	<10	<10	15	<10	82	2
85273	1.7	0.38	52	218	<0.5	<5	3.48	27	7	72	110	3.28	<1	0.33	<10	0.81	2072	2	0.01	1	678	988	1.39	<5	2	207	<5	<0.01	<10	<10	7	26	3135	2
85274	0.7	0.43	52	213	<0.5	<5	3.12	1	8	55	13	3.00	<1	0.34	<10	0.74	1967	<2	0.01	2	776	21	1.00	<5	2	177	<5	<0.01	<10	<10	7	<10	72	1
85275	173.0	0.96	193	216	<0.5	79	4.83	5	17	21	3519	3.36	4	0.20	<10	0.17	640	65	0.03	33	657	234	1.39	209	2	185	<5	0.06	<10	<10	22	20	264	9
85276	0.5	0.62	51	134	<0.5	<5	2.57	1	10	70	15	3.56	<1	0.40	<10	0.72	2048	2	0.01	1	893	49	1.65	<5	3	125	<5	<0.01	<10	<10	12	<10	136	2
85277	0.9	0.54	85	118	<0.5	<5	4.00	2	9	56	39	3.60	<1	0.29	<10	0.70	2147	<2	0.01	1	818	65	1.95	<5	3	165	<5	<0.01	<10	<10	14	<10	140	2
85278	0.6	1.63	37	117	<0.5	<5	2.82	2	10	58	24	3.85	<1	0.33	<10	0.81	1833	3	0.01	1	860	235	1.10	<5	4	105	<5	<0.01	<10	<10	38	<10	285	2
85279	0.6	1.31	24	95	<0.5	<5	4.43	<1	10	58	43	3.62	<1	0.26	<10	0.64	1971	<2	0.01	2	870	13	1.04	<5	3	132	<5	<0.01	<10	<10	36	<10	77	2
85280	0.9	0.49	48	81	<0.5	<5	8.79	1	7	40	20	2.89	<1	0.28	<10	0.57	3112	2	0.01	1	706	10	1.21	<5	3	310	<5	<0.01	<10	<10	14	<10	60	1
85281	0.8	0.55	96	191	<0.5	<5	3.63	2	9	77	18	3.33	<1	0.28	<10	0.60	2240	2	0.01	2	767	67	1.74	<5	2	161	<5	<0.01	<10	<10	17	<10	86	2
85282	0.6	1.36	33	312	<0.5	<5	4.12	2	10	38	28	3.78	<1	0.36	<10	0.73	2186	2	0.01	1	978	55	0.81	<5	3	163	<5	<0.01	<10	<10	30	<10	268	2
85283	<0.2	1.93	20	134	<0.5	<5	3.53	<1	11	49	20	3.79	<1	0.38	11	0.70	1777	<2	0.01	1	993	15	0.61	<5	4	109	<5	<0.01	<10	<10	45	<10	99	2
85284	0.7	0.71	61	118	<0.5	<5	4.64	2	10	39	21	3.37	<1	0.39	<10	0.65	2467	2	0.01	1	914	35	1.09	<5	3	288	<5	<0.01	<10	<10	11	<10	164	2
85285	1.5	0.81	85	112	<0.5	<5	3.06	28	9	41	47	3.81	<1	0.35	<10	0.62	1888	2	0.01	1	860	303	1.93	<5	3	267	<5	<0.01	<10	<10	13	22	2815	2
85286	<0.2	1.88	29	108	<0.5	<5	2.42	2	10	47	21	3.83	<1	0.34	<10	0.84	1858	3	0.01	1	940	21	0.82	<5	5	105	<5	0.01	<10	<10	44	<10	246	2
85287	0.7	1.68	87	108	<0.5	<5	2.64	2	9	53	33	3.86	<1	0.27	<10	0.81	2505	3	0.01	1	907	121	1.70	<5	3	102	<5	<0.01	<10	<10	39	<10	199	2
85288	0.9	1.26	133	112	<0.5	<5	2.84	5	10	56	36	3.96	<1	0.33	<10	0.69	2453	2	0.01	1	825	185	2.65	<5	3	106	<5	<0.01	<10	<10	26	<10	429	2
85289	1.9	1.03	164	112	<0.5	<5	2.62	5	10	68	61	3.67	<1	0.31	<10	0.64	2622	2	0.01	2	828	537	2.01	<5	3	113	<5	<0.01	<10	<10	21	<10	325	2
85290	1.1	1.58	88	130	<0.5	<5	2.17	2	9	68	59	3.59	<1	0.29	<10	0.72	2832	2	0.01	1	801	66	1.73	<5	3	85	<5	<0.01	<10	<10	39	<10	191	2
85291	1.5	0.49	121	83	<0.5	<5	2.55	4	6	115	15	2.58	<1	0.19	<10	0.17	1601	2	0.01	3	468	329	2.56	<5	1	81	<5	<0.01	<10	<10	12	<10	402	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2821RJ

Date : Aug-20-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment 15

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
85292	1.1	0.44	165	93	<0.5	<5	3.50	5	6	98	17	2.67	<1	0.20	<10	0.13	1563	2	0.01	1	453	303	2.93	<5	1	86	<5	<0.01	<10	<10	13	<10	356	1
85293	1.0	0.37	238	120	<0.5	<5	2.13	6	8	113	20	3.25	<1	0.20	<10	0.10	899	2	0.01	3	694	131	3.77	<5	1	57	<5	<0.01	<10	<10	16	<10	289	2
85294	1.4	0.30	148	95	<0.5	<5	2.97	6	5	88	18	2.36	<1	0.19	<10	0.06	1469	3	0.01	1	502	325	2.64	<5	1	113	<5	<0.01	<10	<10	7	<10	465	1
85295	1.4	1.23	94	115	<0.5	<5	2.94	3	10	98	48	3.10	<1	0.23	<10	0.61	3943	2	0.01	3	901	75	1.67	<5	3	95	<5	<0.01	<10	<10	31	<10	307	2
85296	2.3	1.24	78	85	<0.5	<5	3.82	2	8	86	88	3.38	1	0.18	<10	0.64	4325	3	0.01	2	735	87	1.34	<5	3	83	<5	<0.01	<10	10	36	<10	226	1
85297	2.8	1.22	122	89	<0.5	<5	4.89	4	8	81	91	3.28	<1	0.20	<10	0.61	4176	2	0.01	2	699	154	1.53	<5	3	116	<5	<0.01	<10	<10	32	<10	432	2
85298	5.4	0.52	249	71	<0.5	<5	7.20	19	5	66	138	3.14	<1	0.13	<10	0.32	2776	<2	0.01	2	457	1371	2.84	<5	2	182	<5	<0.01	<10	<10	17	15	1858	1
85299	0.8	1.27	63	106	<0.5	<5	2.63	3	10	83	48	3.92	<1	0.24	<10	0.80	1860	3	0.01	1	782	177	0.91	<5	4	107	<5	0.01	<10	<10	39	<10	311	2
85300	<0.2	1.00	<5	272	0.7	<5	0.54	<1	9	112	<1	2.33	<1	0.52	<10	0.66	643	<2	0.06	6	776	10	0.01	<5	2	47	5	0.13	<10	<10	42	<10	64	2
85301	0.3	1.04	24	191	<0.5	<5	2.95	1	10	53	39	3.88	<1	0.28	<10	0.84	1666	4	0.02	1	889	14	0.79	<5	4	165	<5	<0.01	<10	<10	31	<10	120	2
85302	<0.2	1.22	24	155	<0.5	<5	3.47	<1	10	53	25	3.96	<1	0.29	11	0.89	1665	2	0.02	1	1012	18	0.62	<5	5	203	<5	0.01	<10	<10	37	<10	92	2
85303	<0.2	0.95	9	158	<0.5	<5	3.14	<1	10	42	19	3.88	<1	0.34	12	0.93	1481	2	0.03	1	1060	8	0.38	<5	6	235	<5	0.01	<10	<10	29	<10	93	2
85304	<0.2	1.41	9	121	<0.5	<5	2.88	<1	10	59	33	3.90	<1	0.28	11	0.82	1365	<2	0.02	2	916	28	0.41	<5	4	119	<5	0.01	<10	<10	41	<10	120	2
85305	0.2	1.54	8	127	0.5	<5	2.49	<1	11	74	32	4.00	<1	0.21	<10	0.90	1266	3	0.03	1	855	6	0.34	<5	4	105	<5	0.06	<10	<10	48	<10	102	2
85306	0.2	1.39	19	89	<0.5	<5	2.81	<1	11	65	37	4.00	<1	0.22	<10	0.82	1650	3	0.02	2	888	7	0.49	<5	5	96	<5	0.02	<10	<10	49	<10	124	2
85307	0.7	1.67	30	99	<0.5	<5	3.12	1	14	47	85	4.76	<1	0.22	<10	0.81	1821	5	0.02	2	888	8	0.60	<5	4	104	<5	0.03	<10	<10	67	<10	189	2
85308	1.3	1.60	76	58	<0.5	<5	5.03	2	13	99	78	4.23	<1	0.16	<10	1.00	2333	11	0.01	8	819	13	0.86	<5	6	125	<5	0.01	<10	<10	57	<10	175	2
85309	4.6	1.40	125	196	<0.5	<5	5.27	7	12	69	121	4.32	<1	0.21	<10	0.86	2451	4	0.01	5	783	202	1.56	<5	4	127	<5	<0.01	<10	<10	50	<10	705	2
85310	1.5	1.36	184	86	<0.5	<5	4.92	4	12	105	95	3.89	<1	0.20	<10	0.82	2371	4	0.01	6	784	90	1.28	<5	4	122	<5	<0.01	<10	<10	48	<10	169	2
85311	1.3	0.79	113	281	<0.5	<5	3.09	5	8	73	39	3.62	<1	0.22	<10	0.56	1725	4	0.01	2	660	68	1.39	<5	2	84	<5	<0.01	<10	<10	20	<10	386	1
85312	2.8	0.80	116	72	<0.5	<5	11.26	6	11	68	81	3.62	<1	0.18	<10	0.60	2960	3	0.01	6	631	45	1.59	<5	4	237	<5	<0.01	<10	<10	30	<10	495	1
85313	1.5	0.93	54	140	<0.5	<5	6.95	2	11	49	55	3.39	<1	0.27	<10	0.69	2317	3	0.01	2	749	71	0.97	<5	3	222	<5	<0.01	<10	<10	23	<10	247	1
85314	0.3	1.51	20	92	<0.5	<5	4.18	<1	12	42	87	4.53	<1	0.25	<10	0.91	1619	3	0.02	2	954	12	0.53	<5	4	176	<5	<0.01	<10	<10	51	<10	122	2
85315	1.2	2.15	9	95	0.5	<5	4.07	<1	14	27	117	5.08	<1	0.21	<10	1.36	1778	3	0.02	2	955	8	0.39	<5	5	136	<5	0.06	<10	<10	79	<10	139	3
85316	1.3	1.57	24	107	<0.5	<5	3.74	1	13	42	95	4.20	<1	0.27	<10	0.77	2029	4	0.02	2	917	35	0.77	<5	3	191	<5	<0.01	<10	<10	54	<10	222	2
85317	2.3	1.74	98	98	<0.5	<5	4.18	4	14	24	110	5.13	<1	0.23	<10	0.90	2364	2	0.02	1	991	160	1.49	<5	4	108	<5	0.02	<10	<10	69	<10	343	2
85318	2.7	1.42	43	85	<0.5	<5	4.98	1	11	35	129	4.11	<1	0.26	<10	0.67	2115	3	0.01	3	858	38	0.95	<5	3	126	<5	<0.01	<10	<10	48	<10	178	2
85319	2.9	1.03	149	95	<0.5	<5	3.02	9	12	44	166	4.44	<1	0.29	<10	0.67	1641	6	0.01	3	838	414	1.36	<5	4	147	<5	<0.01	<10	<10	31	<10	841	2
85320	2.1	1.35	70	143	<0.5	<5	3.67	6	13	56	81	4.46	<1	0.23	<10	0.82	2133	6	0.01	1	895	157	1.49	<5	3	170	<5	<0.01	<10	<10	37	<10	621	2
85321	0.9	1.81	37	96	0.6	<5	3.63	1	12	31	52	4.75	<1	0.25	<10	0.89	1631	2	0.02	2	1137	17	0.45	<5	4	111	<5	0.03	<10	<10	55	<10	216	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2821RJ

Date : Aug-20-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment 15

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
85322	0.9	1.71	28	106	<0.5	<5	3.32	1	12	45	84	4.69	<1	0.28	<10	0.85	1681	6	0.02	4	1020	40	0.65	<5	4	114	<5	0.01	<10	<10	47	<10	214	2
85323	1.2	1.76	33	124	<0.5	<5	3.13	1	14	45	116	4.83	<1	0.30	<10	0.97	1677	8	0.02	2	1063	25	0.77	<5	4	132	<5	0.02	<10	<10	49	<10	196	2
85324	1.4	1.67	<5	150	0.8	<5	1.91	<1	18	56	151	3.81	<1	0.17	<10	1.03	1181	8	0.03	3	1067	8	0.18	<5	4	137	<5	0.15	<10	<10	70	<10	160	2
85325	>200.0	0.65	547	201	<0.5	126	0.56	21	8	21	7567	2.47	6	0.16	<10	0.62	313	529	0.03	4	487	1009	1.34	1525	2	81	<5	0.05	<10	<10	26	<10	1090	2
85326	1.3	1.52	16	124	<0.5	<5	2.55	1	11	40	59	3.89	<1	0.32	10	0.74	1404	6	0.02	2	927	10	0.48	<5	4	96	<5	0.02	<10	<10	41	<10	163	2
85327	1.7	1.26	133	107	<0.5	<5	4.71	4	12	40	48	4.42	<1	0.29	<10	0.72	2326	6	0.01	1	880	145	1.96	<5	3	142	<5	0.01	<10	<10	37	<10	299	2
85328	1.0	1.49	111	103	<0.5	<5	6.15	12	13	25	72	4.49	<1	0.24	<10	0.76	2703	7	0.01	2	994	90	1.72	<5	3	121	<5	0.04	<10	<10	60	10	1107	2
85329	1.0	1.58	35	86	0.5	<5	9.43	1	14	31	68	4.52	<1	0.28	<10	0.62	2904	7	0.01	2	944	13	0.85	<5	4	175	<5	0.05	<10	<10	53	<10	180	3
85330	0.5	1.54	15	118	0.8	<5	6.47	1	13	49	54	3.94	<1	0.30	<10	0.53	2044	6	0.02	2	897	65	0.44	<5	3	135	<5	0.09	<10	<10	44	<10	145	5
85331	0.9	1.83	<5	142	1.0	<5	4.46	<1	17	18	146	3.99	<1	0.33	<10	1.03	1507	20	0.02	2	1164	7	0.27	<5	4	107	<5	0.15	<10	<10	64	<10	143	4
85332	3.6	0.89	253	114	<0.5	<5	3.94	5	11	38	62	3.33	<1	0.19	<10	0.53	2227	<2	0.01	2	687	15	1.79	<5	2	105	<5	<0.01	<10	<10	45	<10	47	2
85333	2.7	0.85	154	95	<0.5	<5	4.14	3	12	8	24	3.34	<1	0.26	<10	0.40	1221	<2	0.01	1	947	41	2.70	<5	1	158	<5	<0.01	<10	<10	17	<10	76	1
85334	0.7	1.44	71	118	<0.5	<5	4.42	1	16	9	22	4.30	<1	0.38	<10	0.75	1368	<2	0.01	1	1166	33	2.16	<5	2	150	<5	<0.01	<10	<10	24	<10	56	2
85335	0.9	1.51	119	201	<0.5	<5	4.49	2	15	7	37	3.86	<1	0.36	<10	0.80	1418	<2	0.01	1	1193	37	1.39	<5	2	129	<5	0.01	<10	<10	28	<10	70	2
85336	1.2	1.66	70	190	<0.5	<5	4.44	1	17	8	71	4.13	<1	0.36	<10	0.98	1353	<2	0.01	1	1473	37	1.46	<5	2	118	<5	0.02	<10	<10	38	<10	55	2
85337	2.0	1.67	76	114	<0.5	<5	6.82	2	13	9	69	4.26	<1	0.30	<10	0.86	2362	6	0.02	1	1132	110	1.15	<5	2	184	<5	<0.01	<10	<10	36	<10	180	2
85338	0.5	1.80	112	131	<0.5	<5	4.81	2	16	7	31	4.97	<1	0.32	<10	0.93	1875	<2	0.02	1	1250	67	1.78	<5	2	164	<5	<0.01	<10	<10	41	<10	105	2
85339	1.3	1.58	59	139	<0.5	<5	4.31	1	15	8	46	4.41	<1	0.37	<10	0.81	1559	4	0.01	1	1308	62	1.89	<5	2	144	<5	0.03	<10	<10	31	<10	101	2
85340	0.8	0.90	32	148	<0.5	<5	14.95	1	10	10	34	2.25	<1	0.25	10	0.45	3687	<2	0.01	1	731	58	0.78	<5	1	262	<5	<0.01	<10	<10	18	<10	71	1
85341	0.9	1.89	33	140	<0.5	<5	3.51	2	23	8	41	4.01	<1	0.37	<10	1.08	1805	2	0.02	2	1419	147	0.52	<5	2	112	<5	0.03	<10	<10	41	<10	125	2
85342	1.2	2.54	210	106	<0.5	<5	4.87	3	37	11	51	8.35	<1	0.26	<10	1.56	2582	74	0.02	4	1149	89	3.54	<5	4	154	<5	0.03	<10	<10	117	<10	107	3
85343	0.7	2.52	48	117	<0.5	<5	6.02	1	25	14	33	5.95	<1	0.28	<10	1.48	2762	28	0.02	2	1155	77	1.10	<5	3	174	<5	0.05	<10	<10	71	<10	86	3
85344	1.6	1.89	71	146	0.6	<5	5.14	2	21	5	108	5.29	<1	0.42	<10	0.98	2158	4	0.01	1	1418	31	2.13	<5	3	171	<5	0.08	<10	<10	56	<10	185	3
85345	1.7	1.23	315	133	0.5	<5	7.07	5	21	22	24	5.76	<1	0.53	<10	0.51	2282	4	0.01	2	1442	64	>5.00	<5	3	213	<5	0.06	<10	<10	33	<10	97	3
85346	2.5	2.21	62	154	0.6	<5	4.24	1	23	5	70	6.23	<1	0.46	<10	1.21	2354	<2	0.01	1	1482	35	2.65	<5	4	150	<5	0.08	<10	<10	73	<10	104	3
85347	4.7	1.52	157	126	0.6	<5	5.12	2	25	9	115	6.19	<1	0.45	<10	0.68	1876	3	0.01	2	1594	73	4.81	<5	3	197	<5	0.07	<10	<10	48	<10	89	3
85348	11.3	0.63	219	138	<0.5	<5	6.50	6	13	81	83	3.40	<1	0.43	<10	0.09	1770	3	0.01	2	777	189	3.98	<5	2	174	<5	0.01	<10	<10	16	<10	421	2
85349	2.1	0.56	215	98	<0.5	<5	10.68	4	9	37	38	2.66	<1	0.21	<10	0.28	2686	7	0.01	1	618	29	2.23	<5	1	304	<5	<0.01	<10	<10	23	<10	116	1
85350	<0.2	1.21	<5	324	1.0	<5	0.73	<1	10	214	1	2.64	<1	0.56	12	0.66	736	2	0.09	9	802	16	0.02	<5	3	66	7	0.16	<10	<10	48	<10	67	3
85351	5.0	1.08	914	144	<0.5	<5	3.44	17	16	41	168	4.29	<1	0.32	<10	0.50	1623	10	0.01	2	1033	73	3.03	9	2	129	<5	<0.01	<10	<10	39	<10	248	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2821RJ

Date : Aug-20-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment 15

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
85352	9.5	0.60	371	102	<0.5	<5	5.18	27	16	101	299	5.31	<1	0.35	<10	0.13	1602	4	0.01	3	924	1766	>5.00	<5	2	135	<5	0.01	<10	<10	23	20	2481	2
85353	4.6	0.59	250	119	<0.5	<5	8.45	5	12	35	142	3.20	<1	0.28	<10	0.22	2543	11	0.01	1	835	78	3.20	<5	2	244	<5	0.01	<10	<10	19	<10	230	1
85354	<0.2	0.95	<5	160	0.5	<5	0.98	<1	6	112	3	1.80	<1	0.34	29	0.32	290	<2	0.05	8	653	23	0.03	<5	2	36	9	<0.01	<10	<10	17	<10	55	6
85355	<0.2	0.83	<5	135	<0.5	<5	1.02	<1	6	60	2	1.67	<1	0.29	29	0.31	286	<2	0.04	5	637	28	0.02	<5	2	39	10	<0.01	<10	<10	17	<10	64	8
85356	<0.2	0.80	<5	175	0.5	<5	1.41	<1	6	95	2	1.64	<1	0.32	29	0.28	278	<2	0.05	5	633	12	0.02	<5	2	58	9	<0.01	<10	<10	14	<10	37	6
85357	<0.2	0.71	<5	151	<0.5	<5	1.93	<1	5	59	2	1.53	<1	0.28	27	0.30	312	<2	0.04	4	581	12	0.08	<5	2	110	10	<0.01	<10	<10	11	<10	32	6
85358	0.4	1.10	17	377	0.6	<5	1.27	<1	9	69	33	3.13	<1	0.50	19	0.23	945	2	0.03	3	978	16	0.39	<5	3	62	6	<0.01	<10	<10	20	<10	58	4
85359	0.3	0.64	<5	184	<0.5	<5	2.67	<1	9	36	21	2.13	<1	0.35	17	0.51	803	2	0.03	4	886	16	0.25	<5	2	170	<5	<0.01	<10	<10	12	<10	60	4
85360	1.0	0.57	8	441	0.5	<5	2.60	<1	10	37	33	2.14	<1	0.36	14	0.25	1210	4	0.03	3	909	17	0.43	<5	2	159	<5	<0.01	<10	<10	10	<10	70	4
85361	6.0	0.43	350	90	<0.5	<5	2.41	7	11	72	90	4.14	<1	0.28	<10	0.21	852	3	0.01	2	873	47	4.36	<5	1	102	<5	<0.01	<10	<10	9	<10	225	2
85362	1.1	0.72	20	215	0.5	<5	3.10	<1	7	101	7	2.51	<1	0.43	11	0.15	1672	2	0.02	4	676	16	0.12	<5	2	56	<5	<0.01	<10	<10	9	<10	45	3
85363	0.8	0.53	22	215	<0.5	<5	2.66	<1	8	56	6	2.56	<1	0.33	10	0.25	1668	<2	0.02	4	791	15	0.17	<5	2	60	<5	<0.01	<10	<10	7	<10	54	3
85364	2.0	0.46	15	67	0.5	<5	6.09	<1	10	22	13	3.74	<1	0.31	<10	1.41	2716	<2	0.01	3	975	14	0.30	<5	2	282	<5	<0.01	<10	<10	10	<10	82	2
139281	126.8	0.14	358	35	<0.5	5	0.06	118	4	133	293	8.00	50	0.07	<10	0.03	34	3	0.01	<1	255	>10000	>5.00	54	<1	7	<5	<0.01	<10	<10	4	119	>10000	3
139282	101.8	0.18	345	26	<0.5	5	0.39	228	5	109	904	9.77	50	0.05	<10	0.06	170	<2	0.01	<1	265	>10000	>5.00	44	<1	21	<5	<0.01	<10	<10	5	224	>10000	3
139283	127.4	0.10	504	17	<0.5	6	0.05	211	6	154	1250	12.44	42	0.04	<10	0.02	23	3	<0.01	<1	355	9496	>5.00	57	<1	3	<5	<0.01	<10	<10	4	225	>10000	4
139284	126.3	0.17	405	14	<0.5	6	0.02	335	5	135	1836	14.43	64	0.04	<10	0.06	47	<2	<0.01	<1	414	>10000	>5.00	58	<1	2	<5	<0.01	<10	<10	5	357	>10000	6
139285	168.3	0.11	351	36	<0.5	<5	0.56	21	3	168	133	3.63	5	0.05	<10	0.02	191	5	0.01	2	202	1541	3.53	17	<1	12	<5	<0.01	<10	<10	3	18	2513	1
139286	176.5	0.21	491	57	<0.5	<5	0.13	24	8	116	64	4.96	4	0.09	<10	0.02	54	5	0.01	3	449	1194	>5.00	10	1	4	<5	<0.01	<10	<10	5	21	2747	2
139287	47.9	0.41	236	130	<0.5	<5	0.05	4	2	62	12	4.63	1	0.17	<10	0.06	33	3	0.01	<1	1246	189	0.32	14	1	9	<5	0.02	<10	<10	14	<10	157	2
139288	12.2	0.64	253	171	<0.5	<5	0.10	5	3	42	13	4.83	<1	0.21	<10	0.14	99	2	0.01	<1	1291	66	0.74	7	2	6	<5	0.04	<10	<10	18	<10	113	2
139289	>200.0	0.27	281	131	<0.5	<5	0.04	15	4	117	42	4.56	4	0.14	<10	0.02	50	4	0.01	1	709	1536	1.77	39	1	3	<5	0.06	<10	<10	10	13	1670	2
139290	>200.0	0.50	318	88	<0.5	<5	0.07	25	4	126	60	4.21	5	0.10	<10	0.16	247	5	0.01	2	448	3495	2.20	67	1	4	<5	0.01	<10	<10	10	25	3346	2
139291	23.0	1.49	179	129	<0.5	<5	0.20	8	9	90	32	5.28	1	0.18	<10	0.59	846	2	0.01	1	1020	1085	1.14	6	3	3	<5	0.06	<10	<10	26	<10	942	2
139292	>200.0	0.34	1270	49	<0.5	<5	0.03	50	4	163	162	5.55	4	0.11	<10	0.09	92	10	0.01	3	357	2025	>5.00	131	1	3	<5	<0.01	<10	<10	7	36	5000	2
139293	>200.0	0.17	1410	52	<0.5	<5	0.01	48	4	152	87	6.27	4	0.10	<10	0.02	24	11	0.01	1	262	2634	>5.00	115	<1	2	<5	<0.01	<10	<10	3	30	4010	2
139294	>200.0	0.27	1355	104	<0.5	<5	0.02	36	4	126	91	4.29	2	0.13	<10	0.04	51	8	0.01	2	379	1693	3.41	115	1	2	<5	<0.01	<10	<10	5	16	2112	2
139295	>200.0	0.52	916	86	<0.5	<5	0.05	61	5	123	476	5.02	7	0.13	<10	0.18	185	10	0.01	1	608	3834	4.03	306	1	2	<5	<0.01	<10	<10	13	45	6338	2
139296	>200.0	0.18	3526	92	<0.5	<5	0.01	69	3	96	42	5.10	2	0.12	<10	0.01	33	4	0.01	1	430	2747	3.70	197	1	5	<5	<0.01	<10	<10	4	<10	649	2
139297	>200.0	0.16	3609	152	<0.5	<5	0.01	69	2	134	29	4.76	3	0.10	<10	0.02	40	4	<0.01	1	338	1725	1.91	246	1	2	<5	<0.01	<10	<10	5	<10	291	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2821RJ

Date : Aug-20-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment 15

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139298	152.1	0.14	2506	74	<0.5	<5	<0.01	50	3	125	49	5.63	1	0.08	<10	0.01	48	5	<0.01	2	239	1020	4.44	145	<1	1	<5	<0.01	<10	<10	2	<10	882	2
139299	158.5	0.14	2836	143	<0.5	<5	<0.01	53	1	150	19	3.69	1	0.09	<10	0.01	11	8	0.01	1	293	1367	0.71	99	<1	3	<5	<0.01	<10	<10	3	<10	161	1
139300	9.6	2.24	251	64	<0.5	5	0.52	137	19	33	200	8.69	1	0.21	<10	1.39	2836	13	0.01	1	729	2284	>5.00	<5	4	12	<5	0.02	<10	12	81	138	>10000	4
139301	9.7	1.95	210	95	<0.5	<5	0.21	25	14	53	157	8.60	2	0.19	<10	1.19	2200	7	0.01	1	644	1349	3.35	<5	3	9	<5	0.02	<10	<10	83	24	3184	3
139302	9.4	1.84	205	92	<0.5	<5	0.43	17	14	45	175	8.39	<1	0.27	<10	0.97	1909	8	0.01	3	667	2338	4.37	<5	3	11	<5	0.03	<10	<10	67	17	2057	4
139303	3.6	2.56	240	78	<0.5	<5	1.21	43	20	38	135	9.09	<1	0.34	<10	1.42	3152	11	0.01	3	604	896	>5.00	<5	4	29	<5	0.04	<10	12	76	41	5242	4
139304	7.2	3.45	209	81	<0.5	<5	1.56	43	22	22	146	9.97	<1	0.27	<10	1.91	3870	2	0.01	6	892	2896	>5.00	<5	5	38	<5	0.05	<10	16	109	41	5134	4
139305	6.2	2.49	199	100	<0.5	<5	1.70	33	23	36	177	8.22	<1	0.28	<10	1.49	3396	5	0.01	7	1193	2843	4.42	<5	5	41	<5	0.03	<10	13	101	30	3855	3
139306	2.8	2.86	149	119	<0.5	<5	0.37	5	28	254	73	6.67	<1	0.25	<10	1.73	3918	<2	0.01	32	1497	625	0.66	<5	11	4	<5	0.01	<10	15	138	<10	377	3
139307	2.7	2.98	132	120	<0.5	<5	0.47	6	32	242	119	7.30	<1	0.27	<10	1.86	4445	<2	0.01	29	1378	776	1.62	<5	13	7	<5	0.01	<10	18	145	<10	474	3
139308	1.1	1.11	100	157	<0.5	<5	0.33	5	7	101	58	4.53	<1	0.22	<10	0.63	2351	<2	0.01	3	757	694	0.48	<5	3	5	<5	0.01	<10	<10	38	<10	612	3
139309	7.6	1.65	258	147	<0.5	<5	0.26	8	16	174	172	6.77	<1	0.30	<10	0.88	2437	5	0.01	12	1118	3561	2.57	<5	6	5	<5	0.01	<10	<10	71	<10	711	3
139310	10.2	0.79	418	362	<0.5	<5	0.07	9	7	118	80	6.78	<1	0.38	<10	0.36	1784	<2	0.01	3	741	7682	1.09	<5	2	4	<5	<0.01	<10	<10	31	<10	344	3
139311	16.0	1.28	179	95	<0.5	<5	0.22	13	11	162	19	5.87	1	0.29	<10	0.42	390	2	0.01	4	916	942	4.63	<5	3	6	<5	<0.01	<10	<10	25	13	1590	3
139312	47.3	0.35	164	111	<0.5	<5	0.05	3	7	139	5	4.10	<1	0.17	<10	0.02	38	<2	0.01	3	486	141	3.75	6	1	4	<5	<0.01	<10	<10	8	<10	162	2
139313	15.9	1.14	136	83	<0.5	<5	0.14	2	12	200	8	5.96	<1	0.38	<10	0.22	168	2	0.01	5	885	90	>5.00	<5	2	6	<5	<0.01	<10	<10	23	<10	82	3
139314	98.4	1.04	130	139	<0.5	<5	0.25	12	6	190	11	4.84	2	0.23	<10	0.35	303	<2	0.01	4	949	417	2.55	7	2	11	<5	<0.01	<10	<10	19	14	1865	2
139315	75.2	1.17	149	108	<0.5	<5	4.27	9	11	105	27	5.06	2	0.26	<10	0.41	1542	<2	0.01	2	1070	538	4.26	6	2	102	<5	<0.01	<10	<10	18	11	1396	2
139316	>200.0	0.74	291	117	<0.5	<5	0.21	10	7	113	38	5.33	1	0.19	<10	0.22	176	3	0.01	3	981	429	3.50	27	1	8	<5	<0.01	<10	<10	14	<10	903	2
139317	198.7	0.44	407	141	<0.5	<5	0.05	18	6	403	27	3.79	5	0.22	<10	0.02	37	6	0.01	10	280	805	3.42	27	1	3	<5	<0.01	<10	<10	8	15	2035	2
139318	25.1	0.88	374	129	<0.5	<5	0.19	7	7	173	15	3.91	<1	0.18	<10	0.31	222	2	0.01	5	660	105	2.58	8	1	7	<5	<0.01	<10	<10	17	<10	180	2
139319	21.9	0.57	337	166	<0.5	<5	0.06	6	5	378	13	3.34	<1	0.19	<10	0.11	88	5	0.01	10	587	94	1.49	10	1	4	<5	<0.01	<10	<10	14	<10	105	2
139320	38.6	0.59	395	237	<0.5	<5	0.04	8	3	172	19	3.48	1	0.17	<10	0.13	96	<2	0.01	4	674	173	0.36	12	1	8	<5	<0.01	<10	<10	15	<10	239	2
139321	123.8	0.79	240	284	<0.5	<5	0.05	5	3	479	19	3.45	1	0.23	<10	0.17	139	7	0.01	11	495	208	0.41	15	1	17	<5	<0.01	<10	<10	17	<10	227	2
139322	49.8	0.60	362	237	<0.5	<5	0.04	7	3	150	20	3.76	<1	0.18	<10	0.14	121	<2	0.01	3	681	125	0.33	9	1	26	<5	<0.01	<10	<10	15	<10	118	2
139323	29.7	1.40	445	105	<0.5	<5	0.32	10	13	129	27	5.48	<1	0.24	<10	0.49	456	2	0.01	4	900	125	3.73	5	3	9	<5	<0.01	<10	<10	28	<10	366	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2892-RA1

Company: **Ascot Resources Ltd**
 Project: **Dilworth/PO#shipment17**
 Attn: **Sue Deane**

Sep-04-08

We hereby certify the following assay of 22 rock samples submitted Aug-12-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne	Pb %	Zn %
139342	0.19	0.17	1.7			
139343	0.04		2.0			
139344	0.01		0.9			
139345	0.06		1.8			
139346	0.09		3.9			
139347	0.28		6.0			
139348	0.24		5.9			
139349	0.06		1.5			
139350	0.17		3.6			
139351	0.22	0.22	3.2			
139352	0.15		3.5			
139353	0.14		3.7			
139354	0.33		16.1			
139355	1.37		>200	348.8		
139356	4.47		>200	750.3		
139357	1.91		>200	1436	1.18	2.34
139358	0.13		10.8			
139359	1.18		>200	554.2		
139360	1.91		105			
139361	0.50	0.44	17.5			
139362	1.26		>200	480.8		
139363	1.43		144			
*0218	0.89					
*CCu-1c				129.5	0.36	3.93
*BLANK	<0.01			<0.1	<0.01	<0.01

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2892-RA2

Company: **Ascot Resources Ltd**
 Project: **Dilworth/PO#shipment17**
 Attn: **Sue Deane**

Sep-04-08

We hereby certify the following assay of 22 rock samples submitted Aug-12-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
139364	1.61	1.60	110	
139365	0.81		>200	319.0
139366	0.52		>200	665.4
139367	1.23		>200	397.2
139368	0.30		7.1	
139369	0.30		6.6	
139370	0.28		22.9	
139371	0.22		6.8	
139372	0.66		9.4	
139373	0.91	0.89	>200	499.7
139374	0.97		145	
139375	0.93		>200	231.9
139376	1.42		>200	884.1
139377	0.75		97.2	
139378	0.15		16.8	
139379	0.28		21.1	
85484	0.16		2.0	
85485	0.25		1.7	
85486	0.28		1.1	
85487	0.27	0.28	0.6	
85488	0.19		0.9	
85489	1.42		1.5	
*0218	0.92			
*CCu-1c				129.5
*BLANK	<0.01			<0.1

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2892-RA3

Company: **Ascot Resources Ltd**
 Project: **Dilworth/PO#shipment17**
 Attn: **Sue Deane**

Sep-04-08

We hereby certify the following assay of 22 rock samples submitted Aug-12-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne	Pb %	Zn %
85490	0.86	0.90	3.5			
85491	0.32		1.9			
85492	0.17		1.6			
WDR08-09	<0.01		<0.1			
SDO8-11	0.01		<0.1			
SDO8-12	0.02		<0.1			
SDO8-13	0.05		8.8			1.74
SDO8-14	0.07		4.0			
PBSAM3	8.10		>200	4655	1.16	1.27
PBSAM4	0.04	0.04	6.0			
PBSAM5	0.29		17.7			
PBSAM6	0.01		0.4			
PBSAM7	<0.01		1.6			
49451	0.33		10.2			
49452	0.55		5.9			
49453	1.16		170			
49454	0.11		5.1			
49455	0.10		2.3			
49456	0.07		4.9			
49457	0.04	0.06	2.2			
49458	0.23		24.7			
49459	0.11		15.4			
*0218	0.88					
*CCu-1c				129.7	0.35	3.92
*BLANK	<0.01			<0.1	<0.01	<0.01

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2892-RA4

Company: **Ascot Resources Ltd**
Project: Dilworth/PO#shipment17
Attn: Sue Deane

Sep-04-08

We hereby certify the following assay of 14 core samples submitted Aug-12-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
49460	0.11	0.11	8.4
49461	0.11		4.6
49462	0.17		8.0
49463	0.16		4.0
49464	0.06		4.1
49465	0.16		4.2
49466	0.06		2.4
49467	0.05		2.1
49468	0.06		5.7
49469	0.10	0.13	6.9
49470	0.08		8.6
49471	0.07		3.6
49472	0.07		7.4
*0218	0.92		
*BLANK	<0.01		

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2892RJ**

Date : Sep-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment17

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139342	1.7	1.12	362	173	<0.5	<5	0.17	6	6	43	6	3.86	<1	0.26	<10	0.59	562	<2	0.01	1	1038	24	1.24	<5	2	5	<5	<0.01	<10	<10	41	<10	63	2
139343	2.0	0.76	226	140	<0.5	<5	0.13	3	7	58	4	3.57	<1	0.23	<10	0.35	352	<2	0.01	1	1078	42	1.43	<5	2	4	<5	<0.01	<10	<10	29	<10	48	2
139344	0.9	0.73	100	135	<0.5	<5	0.16	1	10	56	5	3.79	<1	0.28	<10	0.27	240	<2	0.01	2	1211	20	2.30	<5	2	4	<5	<0.01	<10	<10	23	<10	43	2
139345	1.8	0.46	102	101	<0.5	<5	0.11	1	10	76	4	3.91	<1	0.24	<10	0.13	120	<2	0.01	2	882	24	3.44	<5	1	3	<5	<0.01	<10	<10	17	<10	27	2
139346	3.9	0.46	373	110	<0.5	<5	0.12	7	6	94	9	3.44	<1	0.20	<10	0.17	161	<2	0.01	2	781	50	2.48	6	1	3	<5	<0.01	<10	<10	14	<10	154	2
139347	6.0	0.30	1376	101	<0.5	<5	0.13	23	4	124	6	4.09	<1	0.14	<10	0.10	139	<2	0.01	2	469	34	2.74	19	1	3	<5	<0.01	<10	<10	11	<10	20	2
139348	5.9	0.66	464	70	<0.5	<5	0.08	7	5	115	3	5.78	<1	0.16	<10	0.38	299	<2	0.01	2	643	36	4.45	13	2	3	<5	<0.01	<10	<10	24	<10	29	3
139349	1.5	0.87	147	112	<0.5	<5	0.14	2	4	70	7	3.35	<1	0.21	<10	0.46	439	<2	0.01	1	1030	17	0.90	<5	2	3	<5	<0.01	<10	<10	28	<10	41	2
139350	3.6	1.53	1160	142	<0.5	<5	0.21	19	7	84	15	3.86	<1	0.25	<10	0.85	789	2	0.01	2	1244	39	0.75	12	3	4	<5	<0.01	<10	<10	47	<10	78	2
139351	3.2	1.04	608	146	<0.5	<5	0.17	11	7	95	17	3.30	<1	0.22	<10	0.54	522	<2	0.01	2	1021	68	1.03	9	2	3	<5	<0.01	<10	<10	35	<10	158	2
139352	3.5	0.68	924	149	<0.5	<5	0.12	15	5	89	7	3.02	<1	0.25	<10	0.27	268	<2	0.01	2	949	42	1.30	11	2	3	<5	<0.01	<10	<10	27	<10	39	2
139353	3.7	0.38	282	128	<0.5	<5	0.15	5	7	133	5	2.53	<1	0.22	<10	0.09	127	<2	0.01	3	385	71	2.17	6	1	7	<5	<0.01	<10	<10	13	<10	61	1
139354	16.1	0.54	1363	98	<0.5	<5	0.12	25	7	122	20	4.63	<1	0.20	<10	0.22	222	<2	0.01	2	764	241	3.72	24	1	3	<5	<0.01	<10	<10	20	<10	397	2
139355	>200.0	0.26	1858	85	<0.5	<5	0.04	32	4	153	39	3.67	<1	0.16	<10	0.06	87	2	0.01	3	577	1386	1.09	123	1	2	<5	<0.01	<10	<10	10	<10	389	2
139356	>200.0	1.07	808	126	<0.5	<5	0.22	26	10	136	198	6.79	<1	0.26	<10	0.42	1427	<2	0.01	2	1284	2069	2.89	35	2	5	<5	<0.01	<10	<10	38	17	2224	3
139357	>200.0	0.21	1096	31	<0.5	6	2.74	209	4	133	860	9.21	1	0.15	<10	0.04	1141	<2	0.01	1	676	>10000	>5.00	99	1	74	<5	<0.01	<10	<10	10	225	>10000	4
139358	10.8	0.77	191	272	<0.5	<5	0.18	5	10	116	45	4.01	<1	0.22	<10	0.23	758	<2	0.02	2	1145	158	1.15	<5	2	6	<5	<0.01	<10	<10	28	<10	404	2
139359	>200.0	0.58	403	80	<0.5	<5	0.17	44	8	142	272	5.74	<1	0.20	<10	0.16	862	<2	0.01	3	777	3507	3.89	14	1	5	<5	<0.01	<10	<10	20	41	5839	3
139360	105.8	0.24	690	146	<0.5	9	0.04	30	2	182	129	3.99	1	0.19	<10	0.04	93	<2	0.01	3	617	1532	2.15	23	1	2	<5	<0.01	<10	<10	11	20	2881	2
139361	17.5	0.14	504	90	<0.5	<5	0.02	23	2	264	62	1.96	<1	0.15	<10	0.01	65	<2	0.01	5	275	685	1.08	10	<1	2	<5	<0.01	<10	<10	4	16	2184	1
139362	>200.0	0.23	1312	136	<0.5	<5	0.03	46	3	232	153	3.86	1	0.17	<10	0.04	87	<2	0.01	4	348	3003	2.77	63	1	4	<5	<0.01	<10	<10	9	30	4220	2
139363	144.0	0.22	678	251	<0.5	<5	0.03	21	2	225	72	2.89	<1	0.22	<10	0.02	65	<2	0.01	4	502	3043	1.15	26	1	8	<5	<0.01	<10	<10	8	12	1557	1
139364	110.3	0.22	758	100	<0.5	<5	0.06	27	3	179	184	2.64	<1	0.16	<10	0.04	112	2	0.01	4	327	4757	1.79	25	<1	15	<5	<0.01	<10	20	9	<10	3623	2
139365	>200.0	0.56	1257	117	<0.5	<5	0.18	5	4	91	72	2.63	1	0.24	<10	0.16	289	<2	0.01	1	678	555	0.76	40	1	8	<5	<0.01	<10	<10	20	<10	719	2
139366	>200.0	0.75	1367	142	<0.5	<5	0.12	3	4	102	42	3.79	<1	0.34	<10	0.17	321	<2	0.01	2	1041	659	0.67	61	2	4	<5	<0.01	<10	<10	28	<10	409	3
139367	>200.0	0.56	3588	120	<0.5	<5	0.12	7	5	80	59	4.68	<1	0.27	<10	0.13	253	<2	<0.01	1	797	689	2.46	61	1	4	<5	<0.01	<10	37	21	<10	1132	3
139368	7.1	0.97	354	192	<0.5	<5	0.16	1	6	91	17	3.70	1	0.40	10	0.27	448	<2	0.01	1	1202	52	0.66	<5	2	6	<5	<0.01	<10	<10	30	<10	64	3
139369	6.6	0.71	194	137	<0.5	<5	0.12	1	5	79	21	3.80	<1	0.32	<10	0.21	323	2	<0.01	1	1161	59	0.61	<5	2	6	<5	<0.01	<10	<10	26	<10	56	2
139370	22.9	0.34	352	104	<0.5	<5	0.04	1	3	147	17	3.49	1	0.22	<10	0.05	193	<2	0.01	2	820	237	0.78	10	1	5	<5	<0.01	<10	<10	15	<10	80	2
139371	6.8	0.65	552	116	<0.5	<5	0.16	1	10	44	17	3.98	<1	0.30	<10	0.25	201	<2	0.01	1	1068	60	2.61	6	2	7	<5	<0.01	<10	<10	26	<10	35	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2892RJ

Date : Sep-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment17

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139372	9.4	0.97	791	87	<0.5	<5	0.20	3	14	83	30	5.49	<1	0.34	<10	0.46	412	<2	0.01	4	1139	120	3.81	9	2	6	<5	<0.01	<10	<10	35	<10	307	4
139373	>200.0	0.43	977	260	<0.5	<5	0.16	1	4	132	41	3.99	2	0.25	<10	0.13	249	2	0.01	2	475	1995	0.58	87	1	11	<5	<0.01	<10	45	21	<10	160	3
139374	145.6	0.46	1558	114	<0.5	<5	0.11	6	6	136	81	4.58	<1	0.25	<10	0.09	228	22	0.01	3	707	798	2.61	53	1	4	<5	<0.01	<10	41	21	<10	855	3
139375	>200.0	0.18	790	91	<0.5	<5	0.03	4	2	197	119	3.37	2	0.13	<10	0.03	108	<2	<0.01	4	227	1068	0.72	64	<1	2	<5	<0.01	<10	12	8	<10	565	2
139376	>200.0	0.25	1525	138	<0.5	<5	0.05	18	3	139	148	4.85	3	0.15	<10	0.05	94	3	<0.01	1	398	2333	1.89	183	<1	2	<5	<0.01	<10	41	13	<10	2653	3
139377	97.2	0.49	2016	165	<0.5	<5	0.13	2	6	130	45	3.46	<1	0.27	<10	0.10	231	3	0.01	3	873	935	1.69	60	1	4	<5	<0.01	<10	<10	18	<10	218	2
139378	16.8	0.60	826	226	<0.5	<5	0.15	1	7	92	17	2.73	<1	0.32	<10	0.12	292	3	0.01	2	1121	152	0.59	14	1	5	<5	<0.01	<10	<10	21	<10	199	2
139379	21.1	0.43	2185	195	<0.5	<5	0.11	1	8	96	17	3.84	<1	0.32	<10	0.03	166	<2	0.01	3	1214	164	0.76	22	1	8	<5	<0.01	<10	12	20	<10	127	3
85484	2.0	2.03	23	110	1.2	<5	2.94	2	21	43	130	5.27	<1	0.09	10	1.32	1219	3	0.03	<1	1303	6	0.22	<5	7	101	5	0.22	<10	<10	128	<10	254	5
85485	1.7	1.90	112	81	0.5	<5	3.07	2	18	61	75	5.64	1	0.14	<10	1.04	1463	2	0.03	3	1210	15	0.66	<5	7	107	5	0.07	<10	<10	125	<10	187	4
85486	1.1	1.88	87	77	0.8	<5	3.64	3	20	38	38	5.12	1	0.16	10	1.08	1897	6	0.03	1	1162	42	0.43	<5	7	108	5	0.12	<10	<10	113	<10	306	4
85487	0.6	2.02	28	90	0.8	<5	3.19	4	19	44	48	5.25	1	0.22	10	1.14	1679	6	0.03	1	1222	83	0.29	<5	7	115	<5	0.10	<10	<10	111	<10	414	5
85488	0.9	2.06	27	89	0.7	<5	3.25	4	19	44	48	5.35	2	0.22	10	1.14	1709	6	0.02	1	1246	82	0.30	<5	7	117	5	0.10	<10	<10	110	<10	414	4
85489	1.5	1.75	160	81	<0.5	<5	1.62	8	15	61	24	5.08	2	0.20	<10	1.01	1850	5	0.01	2	996	346	1.26	<5	4	50	<5	0.04	<10	<10	73	<10	1219	4
85490	3.5	1.05	290	92	<0.5	<5	1.68	20	11	93	87	5.09	<1	0.14	<10	0.83	1705	4	0.01	2	765	488	2.69	<5	3	56	<5	<0.01	<10	<10	57	19	2000	2
85491	1.9	1.33	257	84	<0.5	<5	2.59	5	18	60	114	4.70	<1	0.18	<10	0.79	1798	6	0.01	2	980	112	1.42	<5	5	76	<5	<0.01	<10	<10	76	<10	269	2
85492	1.6	0.81	57	153	<0.5	<5	4.27	1	15	56	131	4.54	<1	0.28	<10	0.75	1830	6	0.01	1	963	19	0.87	<5	6	299	<5	<0.01	<10	<10	33	<10	101	2
WDR08-09	<0.2	0.79	12	100	<0.5	<5	0.27	<1	25	59	20	6.00	<1	0.23	14	0.16	117	<2	0.03	12	1414	22	3.25	<5	3	13	<5	<0.01	<10	<10	39	<10	107	6
SD08-11	<0.2	0.49	10	39	<0.5	<5	0.19	<1	16	38	21	5.90	<1	0.25	28	0.08	140	<2	0.03	9	958	34	>5.00	<5	2	6	6	<0.01	<10	<10	17	<10	83	4
SD08-12	<0.2	0.51	11	97	<0.5	<5	2.58	<1	10	49	7	4.00	<1	0.19	14	0.12	687	<2	0.03	5	1004	18	1.40	<5	4	62	<5	<0.01	<10	<10	13	<10	127	2
SD08-13	8.8	0.72	39	17	1.2	<5	5.55	175	19	106	655	2.13	<1	0.06	<10	0.47	2356	<2	0.01	2	209	238	0.49	<5	2	73	<5	0.01	<10	<10	45	159	>10000	1
SD08-14	4.0	0.64	144	24	<0.5	5	0.11	1	75	47	35	12.17	<1	0.33	<10	0.10	161	506	0.01	24	882	54	>5.00	<5	<1	2	<5	0.02	<10	11	18	<10	188	6
PBSAM3	>200.0	0.14	4177	21	<0.5	5	0.03	179	5	118	357	8.88	5	0.10	<10	0.01	38	5	0.01	1	383	>10000	>5.00	1179	<1	3	<5	<0.01	<10	<10	8	150	>10000	4
PBSAM4	6.0	0.81	49	110	<0.5	<5	0.21	1	10	50	14	3.77	<1	0.22	<10	0.34	272	2	0.01	1	899	32	2.70	<5	2	4	<5	0.04	<10	<10	16	<10	224	2
PBSAM5	17.7	1.64	45	85	<0.5	<5	2.25	17	13	80	122	5.79	<1	0.17	<10	1.02	1759	2	0.01	<1	1178	1991	3.53	6	3	44	<5	0.08	<10	<10	37	15	1543	3
PBSAM6	0.4	1.69	15	142	<0.5	<5	2.81	<1	13	41	16	3.74	<1	0.13	11	1.12	1427	<2	0.03	<1	1107	19	1.46	<5	3	55	<5	0.01	<10	<10	34	<10	70	2
PBSAM7	1.6	0.54	33	121	<0.5	6	0.04	<1	7	36	19	5.40	<1	0.15	<10	0.21	238	<2	0.02	<1	1081	45	2.58	<5	3	6	<5	<0.01	<10	<10	20	<10	110	2
49451	10.2	0.81	1198	109	<0.5	<5	0.43	25	26	68	51	4.17	<1	0.25	<10	0.35	760	<2	0.01	5	1100	52	2.68	6	2	13	<5	<0.01	<10	<10	38	<10	764	2
49452	5.9	1.15	2988	106	<0.5	<5	0.26	54	20	65	51	4.73	<1	0.26	10	0.58	825	<2	0.01	5	1236	48	1.99	15	3	6	<5	<0.01	<10	<10	47	<10	96	2
49453	170.9	0.80	7695	89	<0.5	<5	0.53	172	16	56	65	4.49	<1	0.22	<10	0.41	643	<2	0.01	3	1114	1004	3.02	67	2	16	<5	<0.01	<10	<10	31	37	3987	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment17

Sample type:

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2892RJ

Date : Sep-04-08

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
49454	5.1	0.18	157	75	<0.5	<5	0.02	3	9	106	15	2.53	<1	0.15	<10	0.02	153	<2	0.01	6	553	37	0.74	<5	1	2	<5	<0.01	<10	<10	7	<10	62	1
49455	2.3	1.34	83	107	<0.5	<5	1.47	1	19	38	22	4.75	<1	0.26	<10	1.04	2097	<2	0.01	4	1174	20	3.00	<5	3	83	<5	<0.01	<10	<10	44	<10	137	2
49456	4.9	0.80	174	98	<0.5	<5	0.24	2	18	47	22	5.05	<1	0.23	<10	0.48	800	<2	0.01	5	1106	21	3.79	<5	2	10	<5	<0.01	<10	<10	30	<10	89	2
49457	2.2	1.23	108	101	<0.5	<5	0.97	2	22	25	27	4.95	<1	0.28	<10	0.87	1476	<2	0.01	4	1284	34	3.97	<5	3	54	<5	<0.01	<10	<10	42	<10	195	2
49458	24.7	0.29	364	73	<0.5	<5	0.07	6	12	126	21	4.36	<1	0.22	<10	0.03	36	<2	0.01	4	559	125	4.80	8	1	3	<5	<0.01	<10	<10	11	<10	111	2
49459	15.4	0.27	443	74	<0.5	<5	0.03	7	28	84	33	5.46	<1	0.38	<10	0.02	35	<2	0.02	5	939	122	4.64	7	2	29	<5	<0.01	<10	<10	15	<10	44	2
49460	8.4	0.52	220	104	<0.5	<5	0.25	2	17	101	15	5.11	<1	0.33	<10	0.10	99	<2	0.01	5	1115	40	>5.00	13	2	13	<5	<0.01	<10	47	21	<10	102	4
49461	4.6	0.62	543	163	<0.5	<5	0.15	1	13	82	28	2.52	1	0.42	<10	0.11	165	<2	0.01	5	1066	32	0.71	25	2	6	<5	<0.01	<10	<10	20	<10	22	2
49462	8.0	1.12	367	139	<0.5	<5	0.27	18	11	60	173	3.75	1	0.39	<10	0.33	632	<2	0.01	3	1280	509	1.41	11	2	8	<5	<0.01	<10	<10	33	<10	1911	3
49463	4.0	1.93	297	171	<0.5	<5	0.28	2	18	49	24	4.78	1	0.40	10	0.94	952	<2	0.01	4	1591	83	0.59	5	3	8	<5	<0.01	<10	<10	68	<10	107	4
49464	4.1	1.57	137	107	<0.5	<5	1.40	2	20	54	18	5.81	<1	0.33	<10	1.15	1813	<2	0.01	3	1305	16	3.76	8	3	97	<5	<0.01	<10	<10	50	<10	117	4
49465	4.2	0.63	211	136	<0.5	<5	0.07	2	18	92	16	4.32	<1	0.31	<10	0.25	276	<2	0.01	15	987	28	1.26	6	2	4	<5	<0.01	<10	15	24	<10	32	4
49466	2.4	1.57	153	100	<0.5	<5	0.65	2	24	636	30	6.34	1	0.30	<10	1.13	1868	3	0.01	280	1430	12	4.04	14	3	33	<5	<0.01	<10	<10	50	<10	105	5
49467	2.1	1.77	132	126	<0.5	<5	1.96	2	19	51	16	5.51	<1	0.35	<10	1.31	2509	<2	0.01	4	1320	8	3.49	<5	3	112	<5	<0.01	<10	<10	54	<10	114	4
49468	5.7	1.29	159	91	<0.5	<5	1.03	2	21	59	26	6.50	1	0.33	<10	0.89	1318	<2	0.01	5	1353	20	4.94	10	3	73	<5	<0.01	<10	<10	46	<10	124	5
49469	6.9	1.02	198	93	<0.5	<5	0.21	3	18	49	19	6.23	<1	0.32	<10	0.54	556	<2	0.01	5	1549	21	3.88	10	3	7	<5	<0.01	<10	<10	42	<10	118	5
49470	8.6	0.67	219	87	<0.5	<5	1.62	2	19	62	12	5.45	<1	0.31	<10	0.29	1174	<2	0.01	4	1237	25	>5.00	13	2	49	<5	<0.01	<10	<10	23	<10	89	4
49471	3.6	1.38	116	125	<0.5	<5	3.15	2	21	43	20	5.04	1	0.33	<10	0.99	2412	<2	0.01	4	1370	18	3.74	6	3	232	<5	<0.01	<10	<10	50	<10	79	4
49472	7.4	1.41	111	117	<0.5	<5	2.05	3	21	68	29	5.45	<1	0.30	<10	1.04	2015	<2	0.01	6	1250	69	4.01	11	3	146	<5	0.01	<10	<10	48	<10	166	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-2892-SG1

Company: **Ascot Resources Ltd**
Project: Dilworth/PO#shipment17
Attn: Sue Deane

Sep-04-08

We *hereby certify* the following geochemical analysis of 22 soils samples submitted Aug-12-08

Sample Name	Au ppb
2049	11
2109	10
2281	23
2301	72
2316	22
2340	189
2368	5
2393	18
2414	188
2431	45
2455	10
2478	12
2493	16
2511	51
2526	63
2545	104
2553	30
2573	41
2639	1520
2662	685
2684	665
2702	37
*0218	884
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-2892-SG2

Company: **Ascot Resources Ltd**
Project: Dilworth/PO#shipment17
Attn: Sue Deane

Sep-04-08

We *hereby certify* the following geochemical analysis of 22 soils samples submitted Aug-12-08

Sample Name	Au ppb
2724	527
2745	746
2767	104
2790	107
2821	12
2835	109
2852	123
2872	925
2899	455
2935	240
2947	537
2970	762
2995	794
3029	297
3059	202
3090	1173
3117	294
3144	278
3176	302
3185	545
3225	332
3244	381
*0218	897
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-2892-SG3

Company: **Ascot Resources Ltd**
Project: Dilworth/PO#shipment17
Attn: Sue Deane

Sep-04-08

We *hereby certify* the following geochemical analysis of 22 soils samples submitted Aug-12-08

Sample Name	Au ppb
3264	478
3293	425
3328	462
3389	837
3405	235
3449	143
3464	386
3488	116
3500	86
3523	96
3549	76
3572	32
3596	490
3622	56
3648	120
3668	376
3699	856
3712	455
3737	149
3762	8
3783	85
3837	8
*0218	920
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-2892-SG4

Company: **Ascot Resources Ltd**
Project: Dilworth/PO#shipment17
Attn: Sue Deane

Sep-04-08

We *hereby certify* the following geochemical analysis of 22 soils samples submitted Aug-12-08

Sample Name	Au ppb
3862	583
3886	187
3914	556
3946	4
3974	253
3990	258
3997	6657
4023	21
4048	5
4070	162
4094	163
4117	85
4140	5
4163	62
4188	2
4207	16
4237	266
4263	53
4277	32
4293	13
4308	29
4328	4
*0218	871
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-2892-SG5

Company: **Ascot Resources Ltd**
Project: Dilworth/PO#shipment17
Attn: Sue Deane

Sep-04-08

We *hereby certify* the following geochemical analysis of 22 soils samples submitted Aug-12-08

Sample Name	Au ppb
4354	6
4372	7
4392	4
4410	9
4434	4
4461	6
4477	15
4496	8
4517	5
4539	14
4561	4
4579	10
4599	4
4622	1
4644	5
4666	6
4686	6
4703	5
4727	8
4743	6
4760	3
4781	2
*0218	890
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-2892-SG6

Company: **Ascot Resources Ltd**
Project: Dilworth/PO#shipment17
Attn: Sue Deane

Sep-04-08

We *hereby certify* the following geochemical analysis of 22 soils samples submitted Aug-12-08

Sample Name	Au ppb
4805	5
4830	<1
4847	4
4865	5
4890	8
4902	1
4916	7
4936	8
1979	65
2006	13
2023	29320
2072	24
2094	107
2136	375
2152	24
2180	71
2209	12
2233	31
2256	24
2281	39
2300	66
2332	341
*0218	922
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-2892-SG7

Company: **Ascot Resources Ltd**
Project: Dilworth/PO#shipment17
Attn: Sue Deane

Sep-04-08

We *hereby certify* the following geochemical analysis of 22 soils samples submitted Aug-12-08

Sample Name	Au ppb
2362	20
2387	27
2405	1896
2425	175
2451	522
2469	1288
2489	503
2494	474
2524	194
2552	49
2578	47
2644	4826
2667	163
2692	266
2717	30
2743	244
2771	96
2792	794
2815	130
2827	1482
2856	2165
2883	57
*0218	903
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-2892-SG8

Company: **Ascot Resources Ltd**
Project: Dilworth/PO#shipment17
Attn: Sue Deane

Sep-04-08

We *hereby certify* the following geochemical analysis of 22 soils samples submitted Aug-12-08

Sample Name	Au ppb
2908	13
2932	38
2963	212
2988	188
3014	161
3042	68
3066	22
3090	513
3119	196
3144	116
3167	22
3186	114
3216	39
3239	112
3263	65
3280	489
3308	67
3326	22
3353	261
3377	19
3399	20
3419	265
*0218	921
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-2892-SG9

Company: **Ascot Resources Ltd**
Project: Dilworth/PO#shipment17
Attn: Sue Deane

Sep-04-08

We *hereby certify* the following geochemical analysis of 22 soils samples submitted Aug-12-08

Sample Name	Au ppb
3433	1729
3455	293
3469	72
3486	252
3515	632
3534	670
3567	242
3590	703
3617	273
3639	100
3659	45
3685	340
3712	434
3736	628
3759	67
3786	1209
3813	170
3839	187
3866	210
3888	505
3916	1680
3940	1160
*0218	879
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-2892-SG10

Company: **Ascot Resources Ltd**
Project: Dilworth/PO#shipment17
Attn: Sue Deane

Sep-04-08

We *hereby certify* the following geochemical analysis of 22 soils samples submitted Aug-12-08

Sample Name	Au ppb
3961	371
3979	394
3991	440
4011	80
4038	34
4060	15
4079	53
4101	11
4122	251
4134	1452
4155	23
4176	16
4196	11
4214	323
4238	258
4272	110
4289	320
4313	14
4325	6
4349	4
4378	6
4391	2
*0218	874
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-2892-SG11

Company: **Ascot Resources Ltd**
Project: Dilworth/PO#shipment17
Attn: Sue Deane

Sep-04-08

We *hereby certify* the following geochemical analysis of 22 soils samples submitted Aug-12-08

Sample Name	Au ppb
4417	12
4442	8
4466	1
4493	76
4511	24
4563	50
4597	21
4613	12
4637	4
4667	5
4688	14
4711	15
4732	4
4751	5
4766	12
4788	21
4815	12
4840	10
4861	2
4881	7
4913	1
4945	20
*0218	876
*BLANK	<1

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2892SJ

Date : Sep-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment17

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
2049	0.6	1.79	33	26	<0.5	<5	0.11	1	3	9	8	1.83	<1	0.06	14	0.06	341	3	0.02	3	668	126	0.06	<5	1	4	<5	0.02	<10	<10	18	<10	79	2
2109	4.3	2.91	99	144	<0.5	<5	0.22	1	61	4	55	8.41	<1	0.13	16	0.27	>10000	<2	0.02	3	5911	45	0.20	<5	3	7	<5	0.01	<10	46	62	<10	145	5
2281	2.5	2.65	124	110	<0.5	<5	0.11	2	38	5	74	6.95	<1	0.12	16	0.39	3124	<2	0.02	3	2360	58	0.23	<5	1	4	<5	0.03	<10	<10	71	<10	119	3
2301	5.9	3.41	697	115	<0.5	<5	0.14	12	28	9	125	6.08	<1	0.14	23	0.33	4541	<2	0.01	3	2820	247	0.12	<5	2	2	<5	0.02	<10	14	50	<10	262	5
2316	0.5	1.04	17	45	<0.5	<5	0.06	<1	7	12	7	2.30	<1	0.05	<10	0.29	308	<2	0.01	8	651	30	0.04	<5	1	8	<5	0.05	<10	<10	38	<10	46	1
2340	1.0	2.14	264	81	<0.5	<5	0.02	4	11	3	25	4.44	<1	0.10	<10	0.22	1581	<2	0.01	<1	1334	49	0.09	<5	<1	1	<5	0.02	<10	<10	65	<10	55	2
2368	0.2	0.95	10	33	<0.5	<5	0.05	<1	4	7	551	1.38	<1	0.06	<10	0.10	122	<2	0.01	3	702	32	0.06	<5	1	8	<5	0.06	<10	<10	35	<10	25	1
2393	<0.2	1.41	52	48	<0.5	<5	0.07	1	10	15	10	5.19	<1	0.08	13	0.14	559	3	0.03	4	1311	65	0.13	<5	1	5	<5	0.18	<10	<10	91	<10	70	22
2414	0.3	2.35	62	66	<0.5	<5	0.12	1	11	19	14	4.26	<1	0.07	20	0.42	708	4	0.02	13	1193	56	0.11	<5	1	9	<5	0.08	<10	<10	54	<10	100	7
2431	0.2	2.23	119	130	<0.5	<5	0.27	2	18	19	24	4.67	<1	0.08	22	0.54	2009	3	0.02	22	1330	61	0.05	<5	2	16	<5	0.05	<10	16	50	<10	236	3
2455	0.7	1.04	14	61	<0.5	<5	0.10	<1	5	8	6	2.18	<1	0.05	<10	0.09	257	<2	0.01	2	762	20	0.05	<5	1	12	<5	0.09	<10	<10	79	<10	29	1
2478	0.2	1.98	50	54	<0.5	<5	0.09	1	13	15	15	6.44	<1	0.04	<10	0.32	698	<2	0.02	8	1158	41	0.05	<5	2	13	<5	0.11	<10	<10	89	<10	78	3
2493	1.0	2.32	86	67	<0.5	<5	0.05	1	7	1	8	5.38	<1	0.08	<10	0.33	899	<2	0.02	<1	1571	37	0.06	<5	1	2	<5	0.01	<10	<10	82	<10	60	3
2511	1.7	1.52	864	81	<0.5	<5	0.06	14	36	3	45	8.30	<1	0.16	11	0.19	3937	6	0.01	1	2258	129	0.11	<5	1	2	<5	0.01	<10	12	34	<10	145	5
2526	1.6	2.19	212	212	<0.5	<5	0.19	4	22	15	51	6.01	<1	0.14	39	0.47	2790	<2	0.02	12	1857	105	0.04	<5	3	10	<5	0.02	<10	10	47	<10	509	5
2545	3.8	3.07	512	123	<0.5	<5	0.15	9	37	27	88	5.69	<1	0.07	21	0.75	2794	2	0.01	41	1267	51	0.04	<5	7	12	<5	0.07	<10	13	60	<10	380	4
2553	7.3	2.07	1384	108	<0.5	<5	0.02	24	13	4	35	9.27	<1	0.08	10	0.11	2499	<2	0.02	2	3057	185	0.09	<5	1	2	<5	0.01	<10	<10	117	<10	141	4
2573	1.7	2.52	1832	237	<0.5	<5	0.15	31	25	8	55	9.34	<1	0.09	18	0.34	2496	<2	0.02	3	1839	132	0.11	8	1	10	<5	0.02	<10	<10	79	<10	221	5
2639	30.0	1.73	3645	160	0.8	8	0.03	64	72	2	195	11.19	<1	0.14	27	0.27	8908	4	0.01	2	3169	1115	0.07	12	7	<1	<5	<0.01	<10	35	48	<10	588	9
2662	18.7	1.46	1060	168	0.5	6	0.02	18	51	2	92	9.24	<1	0.13	25	0.26	6045	2	0.01	3	2717	335	0.07	<5	6	<1	<5	<0.01	<10	20	45	<10	315	8
2684	3.5	0.78	1557	102	<0.5	<5	0.02	26	21	3	35	6.42	<1	0.11	21	0.07	2862	<2	0.01	1	2602	111	0.05	7	1	1	<5	0.01	<10	<10	26	<10	79	3
2702	0.2	2.00	86	50	<0.5	<5	0.05	1	9	19	8	5.18	<1	0.06	16	0.20	756	3	0.02	6	884	59	0.07	<5	1	5	<5	0.11	<10	<10	60	<10	64	12
2724	3.5	1.08	542	76	0.6	5	0.02	8	44	1	93	8.52	<1	0.15	28	0.06	4995	<2	0.01	1	3332	130	0.06	<5	3	<1	<5	<0.01	<10	20	20	<10	46	6
2745	9.0	1.12	682	77	<0.5	5	0.01	11	72	3	66	7.81	<1	0.12	22	0.03	7234	<2	0.01	<1	2286	284	0.05	<5	6	<1	<5	<0.01	<10	34	27	<10	33	5
2767	3.8	3.12	155	95	<0.5	<5	0.06	3	37	9	42	7.58	<1	0.10	12	0.15	4553	2	0.02	2	4577	100	0.19	<5	<1	4	<5	0.02	<10	19	77	<10	35	5
2790	1.1	1.90	214	74	<0.5	<5	0.06	3	10	12	41	6.53	<1	0.08	15	0.26	962	4	0.01	7	1976	70	0.08	<5	1	5	<5	0.03	<10	<10	55	<10	47	4
2821	0.3	2.03	15	55	<0.5	<5	0.17	<1	13	18	12	4.85	<1	0.04	10	0.72	496	<2	0.01	16	820	10	0.04	<5	3	15	<5	0.15	<10	<10	63	<10	36	5
2835	2.4	3.13	395	211	<0.5	<5	0.87	8	25	27	46	7.29	<1	0.07	28	0.61	2844	16	0.02	13	1906	72	0.18	<5	3	31	<5	0.11	<10	<10	81	<10	253	6
2852	5.5	1.58	249	79	<0.5	<5	0.05	4	6	4	28	2.85	<1	0.08	10	0.07	851	7	0.02	2	1703	44	0.10	<5	<1	4	<5	0.01	<10	<10	35	<10	18	2
2872	9.1	1.47	1685	277	0.7	<5	0.25	31	38	5	105	9.06	<1	0.14	23	0.49	6544	3	0.01	6	2384	201	0.16	<5	3	13	<5	0.02	<10	30	33	<10	392	7

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2892SJ

Date : Sep-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment17

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
2899	19.4	2.00	1137	130	<0.5	<5	0.04	19	27	6	146	9.77	<1	0.09	12	0.23	7223	13	0.01	2	4773	429	0.14	<5	2	2	<5	0.01	<10	33	78	<10	74	7
2935	5.5	1.84	222	136	<0.5	<5	0.04	4	12	4	32	6.96	<1	0.16	<10	0.14	4990	13	0.01	<1	3288	49	0.10	<5	<1	2	<5	0.02	<10	20	53	<10	70	3
2947	2.8	1.70	1758	86	<0.5	<5	0.03	29	8	6	57	8.96	<1	0.08	10	0.07	811	10	0.01	<1	2211	111	0.08	<5	2	2	<5	0.01	<10	<10	87	<10	32	5
2970	5.0	2.43	959	229	0.8	<5	0.34	19	37	9	265	10.16	<1	0.14	54	0.38	6661	40	0.02	7	3245	558	0.11	<5	4	10	<5	0.03	<10	30	43	10	811	7
2995	9.6	3.07	894	99	<0.5	<5	0.03	14	50	4	136	12.02	<1	0.14	19	0.32	5317	39	0.01	1	5581	258	0.08	<5	3	1	<5	0.02	<10	21	91	<10	177	11
3029	6.5	3.14	198	165	<0.5	<5	0.02	4	33	15	100	7.11	<1	0.13	20	0.19	>10000	81	0.01	3	2240	55	0.11	<5	2	<1	<5	0.02	<10	80	77	<10	172	6
3059	4.5	2.62	218	52	<0.5	<5	0.07	3	27	11	133	7.46	<1	0.14	18	0.33	3773	39	0.01	3	3068	324	0.10	<5	1	7	<5	0.03	<10	15	78	<10	79	4
3090	43.1	1.55	2710	62	<0.5	<5	0.10	47	20	6	296	11.75	<1	0.10	11	0.20	3821	70	0.01	1	8601	2179	0.12	<5	1	5	<5	0.02	<10	13	75	<10	320	7
3117	2.9	1.80	268	187	<0.5	<5	0.47	9	24	13	267	6.08	<1	0.09	18	0.56	2677	51	0.02	13	1786	159	0.09	<5	2	24	<5	0.04	<10	<10	44	<10	460	5
3144	35.6	1.95	285	128	<0.5	<5	0.01	5	9	6	108	6.85	<1	0.08	10	0.07	1017	109	0.01	1	1221	341	0.07	<5	1	1	<5	0.03	<10	<10	64	<10	185	3
3176	4.2	2.92	300	85	<0.5	<5	0.09	5	19	24	166	6.71	<1	0.07	15	0.67	1674	17	0.01	20	1888	110	0.05	<5	4	4	<5	0.05	<10	<10	49	<10	177	7
385	18.6	2.09	634	109	<0.5	7	0.03	12	37	25	306	11.19	<1	0.07	<10	0.17	9785	45	0.01	2	5377	1882	0.14	<5	5	2	<5	0.01	<10	56	87	<10	530	8
3225	4.1	2.02	224	210	1.0	<5	0.52	20	31	20	770	6.76	<1	0.09	49	0.79	4565	18	0.01	29	2029	304	0.12	<5	13	16	<5	0.02	<10	19	51	17	1475	6
3244	2.7	1.51	239	51	<0.5	<5	0.05	3	14	70	98	12.58	<1	0.05	<10	0.14	1437	112	0.01	<1	3873	114	0.05	<5	5	3	<5	0.21	<10	<10	483	<10	55	7
3264	5.1	2.59	82	61	<0.5	<5	0.05	2	22	18	207	6.76	<1	0.10	22	0.20	3961	59	0.02	4	2415	194	0.08	<5	3	1	<5	0.05	<10	10	65	12	286	7
3293	3.4	1.39	850	92	<0.5	7	0.01	15	32	4	215	10.91	<1	0.06	<10	0.30	6869	30	0.01	<1	3783	1076	0.08	<5	1	1	<5	0.01	<10	31	96	<10	374	4
3328	63.8	0.80	1675	106	<0.5	<5	0.07	37	22	1	275	7.26	<1	0.08	14	0.40	4408	25	0.01	<1	1048	1526	0.07	6	2	2	<5	0.01	<10	16	29	<10	724	3
3389	4.9	1.86	1331	62	<0.5	5	0.01	23	37	7	245	10.34	<1	0.07	<10	0.60	6100	20	0.01	1	1820	609	0.06	<5	5	1	<5	0.02	<10	26	105	<10	202	5
3405	9.3	1.50	316	45	<0.5	<5	0.06	7	23	4	208	7.76	<1	0.09	<10	0.56	4758	8	0.01	1	1334	1853	0.10	<5	4	1	<5	0.01	<10	17	70	<10	546	3
3449	3.2	1.82	207	67	<0.5	<5	0.31	5	27	16	83	6.00	<1	0.07	11	0.85	1722	9	0.01	17	1203	412	0.06	<5	3	11	<5	0.05	<10	<10	57	<10	334	3
3464	2.6	0.64	189	89	<0.5	<5	0.06	4	4	1	17	1.00	<1	0.05	<10	0.05	165	3	0.01	<1	383	32	0.03	<5	1	2	<5	0.01	<10	<10	45	<10	45	<1
3488	3.1	1.45	62	107	<0.5	<5	0.41	2	9	6	54	3.99	<1	0.10	<10	0.27	1199	19	0.02	12	1151	556	0.13	<5	1	10	<5	0.03	<10	<10	63	<10	216	1
3500	1.0	0.47	53	53	<0.5	<5	0.04	1	5	1	13	0.81	<1	0.08	<10	0.03	134	<2	0.01	<1	316	7	0.02	<5	<1	1	<5	0.01	<10	<10	17	<10	22	<1
3523	4.0	2.19	106	69	<0.5	<5	0.07	2	15	7	82	6.22	<1	0.07	<10	0.36	1633	19	0.01	1	1266	177	0.10	<5	1	9	<5	0.05	<10	<10	145	<10	158	2
3549	<0.2	2.31	23	62	<0.5	<5	0.07	<1	13	32	48	5.40	<1	0.06	10	0.78	707	10	0.01	40	811	29	0.06	<5	2	9	<5	0.05	<10	<10	68	<10	142	2
3572	1.1	3.07	15	24	<0.5	<5	0.04	<1	5	18	16	6.81	<1	0.07	25	0.09	477	29	0.06	1	765	39	0.09	<5	1	<1	5	0.12	<10	<10	24	<10	77	157
3596	2.7	1.84	402	127	<0.5	<5	0.12	10	36	4	67	7.05	<1	0.14	14	0.53	4987	14	0.01	3	1681	176	0.03	<5	2	3	<5	0.02	<10	17	36	<10	335	3
3622	0.7	2.65	36	70	<0.5	<5	0.15	<1	24	26	35	5.82	<1	0.04	13	0.93	1542	3	0.01	27	686	26	0.04	<5	3	8	<5	0.07	<10	<10	63	<10	194	3
3648	1.9	1.83	161	71	<0.5	<5	0.06	2	12	15	23	6.04	<1	0.10	<10	0.20	2896	23	0.01	3	1493	877	0.11	<5	<1	4	<5	0.05	<10	10	65	<10	307	2
3668	2.3	1.98	543	73	<0.5	<5	0.05	8	39	2	92	9.79	<1	0.13	14	0.68	4116	11	0.01	<1	2900	192	0.09	<5	3	1	<5	0.08	<10	17	51	<10	111	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2892SJ

Date : Sep-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment17

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
3699	3.2	1.81	352	75	<0.5	<5	0.08	8	46	2	400	9.38	<1	0.11	15	0.85	4938	43	0.01	1	2356	67	0.14	<5	6	1	<5	0.10	<10	19	54	<10	366	3
3712	5.2	2.17	382	131	<0.5	<5	0.10	9	54	4	492	8.96	<1	0.13	16	1.05	5328	50	0.01	4	1849	123	0.06	<5	6	2	<5	0.09	<10	20	82	<10	347	3
3737	3.2	1.83	107	47	<0.5	<5	0.04	2	8	21	114	6.16	<1	0.05	<10	0.28	449	27	0.01	9	590	748	0.04	<5	2	5	<5	0.03	<10	<10	80	<10	265	2
3762	1.2	2.97	26	109	<0.5	<5	0.32	<1	20	2	122	6.85	1	0.11	<10	1.32	1915	2	0.01	3	1185	58	0.05	<5	3	10	<5	0.01	<10	<10	93	<10	177	3
3783	2.7	1.54	85	92	<0.5	6	0.01	<1	39	2	80	10.34	<1	0.08	12	0.13	5371	<2	0.01	<1	2122	129	0.07	<5	3	1	<5	<0.01	<10	23	42	<10	133	5
3837	<0.2	0.31	9	199	<0.5	<5	1.37	1	2	2	22	0.52	<1	0.06	<10	0.05	115	<2	0.03	9	1008	20	0.16	<5	1	73	<5	0.01	<10	<10	6	<10	84	1
3862	12.2	1.69	381	104	<0.5	<5	0.27	9	13	14	62	6.03	<1	0.10	13	0.36	1386	3	0.01	12	1250	782	0.06	7	2	14	<5	0.02	<10	<10	32	<10	668	3
3886	18.3	3.14	170	100	<0.5	<5	0.28	4	37	27	41	6.23	<1	0.08	20	0.87	2466	<2	0.03	29	1484	223	0.04	<5	4	16	<5	0.08	<10	<10	58	<10	539	3
3914	6.2	1.85	209	511	<0.5	7	0.38	3	30	4	45	6.45	<1	0.07	18	0.69	5866	2	0.01	3	1952	40	0.25	<5	3	18	<5	0.01	<10	22	27	<10	130	4
3946	1.5	2.86	14	146	<0.5	<5	0.30	<1	10	25	12	4.90	<1	0.06	27	0.49	620	4	0.02	19	739	23	0.08	<5	2	23	<5	0.07	<10	<10	46	<10	210	7
3974	1.0	1.73	64	58	<0.5	<5	0.09	1	11	18	16	4.82	<1	0.08	13	0.54	773	2	0.01	11	965	45	0.05	<5	1	9	<5	0.05	<10	<10	59	<10	90	2
3990	2.1	0.97	54	47	<0.5	<5	0.02	1	2	4	7	1.26	<1	0.08	<10	0.05	68	<2	0.01	<1	1022	14	0.10	<5	1	3	<5	0.01	<10	<10	18	<10	19	2
3997	43.7	0.58	1041	64	<0.5	<5	0.07	19	6	3	93	8.21	<1	0.09	<10	0.05	1433	7	0.01	<1	4430	1322	0.10	23	1	3	<5	0.01	<10	10	18	<10	420	4
4023	4.2	2.10	75	58	<0.5	<5	0.02	<1	5	2	42	6.94	<1	0.07	11	0.61	544	<2	0.01	<1	1537	26	0.07	<5	2	1	<5	<0.01	<10	<10	95	<10	39	3
4048	<0.2	1.63	22	33	<0.5	<5	0.05	<1	14	22	9	7.94	<1	0.06	12	0.42	1685	2	0.01	11	1955	45	0.07	<5	1	6	<5	0.16	<10	<10	74	<10	68	12
4070	2.0	2.22	98	97	<0.5	<5	0.11	2	41	12	89	6.61	<1	0.11	12	0.67	2438	<2	0.02	11	1334	122	0.06	<5	3	6	<5	0.04	<10	<10	59	<10	339	3
4094	13.9	2.11	58	159	<0.5	<5	0.56	2	6	6	22	4.63	<1	0.07	10	0.14	621	6	0.01	1	990	69	0.06	<5	1	26	<5	0.01	<10	<10	69	<10	578	3
4117	4.0	1.76	441	80	<0.5	7	0.11	7	55	3	99	8.73	<1	0.08	13	0.44	2510	<2	0.01	4	1768	43	0.10	<5	3	2	<5	0.01	<10	<10	64	<10	143	4
4140	<0.2	0.95	5	39	<0.5	<5	0.04	<1	8	15	20	2.53	2	0.05	17	0.12	307	2	0.01	4	509	35	0.04	<5	1	5	<5	0.17	<10	<10	63	<10	37	8
4163	9.6	2.05	29	74	<0.5	<5	0.36	1	23	21	81	4.63	1	0.05	16	0.85	962	<2	0.01	26	1063	41	0.02	<5	4	19	<5	0.09	<10	<10	53	<10	276	3
4188	1.6	1.28	10	63	<0.5	<5	0.07	1	6	10	11	2.73	2	0.05	10	0.11	218	<2	0.01	5	641	15	0.05	<5	1	9	<5	0.06	<10	<10	55	<10	50	2
4207	4.5	2.74	12	54	<0.5	<5	0.09	<1	13	18	19	4.48	1	0.03	13	0.42	584	<2	0.01	8	538	17	0.05	<5	2	10	<5	0.08	<10	<10	55	<10	106	4
4237	50.3	0.80	287	33	<0.5	<5	0.11	5	35	1	40	6.68	1	0.05	<10	0.36	2723	12	0.01	<1	1278	1416	0.05	6	5	2	<5	<0.01	<10	11	20	<10	348	3
4263	3.4	2.19	92	60	<0.5	<5	0.03	1	29	4	65	6.04	<1	0.06	11	0.66	3650	<2	0.01	4	1476	31	0.06	<5	3	1	<5	0.01	<10	12	45	<10	150	7
4277	12.6	0.88	73	50	<0.5	<5	0.04	1	18	4	13	3.89	<1	0.06	10	0.12	2386	<2	0.01	1	1734	50	0.07	<5	1	3	<5	0.01	<10	<10	39	<10	43	2
4293	1.4	1.50	25	52	<0.5	<5	0.07	<1	10	15	17	4.69	<1	0.05	<10	0.41	546	<2	0.02	9	555	17	0.05	<5	1	9	<5	0.07	<10	<10	56	<10	56	2
4308	1.6	1.88	28	115	<0.5	<5	0.17	<1	18	16	64	4.34	<1	0.06	11	0.69	1190	<2	0.01	16	975	18	0.03	<5	2	9	<5	0.03	<10	<10	48	<10	104	2
4328	<0.2	1.60	6	88	<0.5	<5	0.35	<1	17	19	21	4.32	<1	0.04	12	0.85	770	<2	0.01	23	1131	11	<0.01	<5	4	18	<5	0.10	<10	<10	55	<10	101	3
4354	0.3	1.29	10	61	<0.5	<5	0.17	<1	14	31	19	3.62	<1	0.05	11	0.76	549	<2	0.01	40	772	12	0.04	<5	3	11	<5	0.02	<10	<10	32	<10	102	2
4372	0.6	1.10	9	74	<0.5	<5	0.24	<1	13	29	18	3.45	<1	0.05	16	0.67	485	<2	0.01	43	1013	12	0.05	<5	3	16	<5	0.02	<10	<10	31	<10	107	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2892SJ

Date : Sep-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment17

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
4392	0.6	1.12	7	41	<0.5	<5	0.07	<1	7	36	12	2.97	<1	0.05	10	0.61	206	<2	0.01	38	698	8	0.03	<5	2	5	<5	0.01	<10	<10	28	<10	66	1
4410	0.4	0.81	5	61	<0.5	<5	0.07	<1	3	14	7	1.85	<1	0.05	<10	0.17	104	<2	0.01	10	723	7	0.05	<5	<1	8	<5	0.01	<10	<10	30	<10	29	1
4434	0.4	1.75	12	101	<0.5	<5	0.14	<1	9	44	14	3.89	<1	0.07	15	0.73	289	<2	0.01	45	879	14	0.04	<5	2	8	<5	0.01	<10	<10	35	<10	85	2
4461	0.2	1.23	6	91	<0.5	<5	0.25	<1	7	16	4	3.04	<1	0.05	<10	0.29	273	2	0.02	7	535	12	0.06	<5	1	21	<5	0.06	<10	<10	68	<10	44	1
4477	0.5	2.74	24	55	<0.5	<5	0.12	<1	35	17	38	6.16	<1	0.06	26	0.30	2047	2	0.03	9	1434	37	0.13	<5	2	4	<5	0.06	<10	<10	35	<10	95	9
4496	0.3	1.51	10	76	<0.5	<5	0.09	<1	8	43	13	3.23	<1	0.06	15	0.75	255	<2	0.01	48	697	14	0.03	<5	2	6	<5	0.01	<10	<10	32	<10	81	2
4517	0.4	1.36	11	85	<0.5	<5	0.15	<1	12	40	11	3.51	<1	0.06	13	0.68	410	<2	0.01	48	847	13	0.02	<5	3	10	<5	0.01	<10	<10	31	<10	111	2
4539	0.4	1.02	7	60	<0.5	<5	0.06	<1	5	33	8	2.53	<1	0.04	<10	0.53	130	<2	0.01	33	544	6	0.03	<5	2	5	<5	0.01	<10	<10	28	<10	62	1
4561	0.2	1.53	6	110	<0.5	<5	0.39	<1	11	17	10	4.27	<1	0.03	<10	0.53	375	<2	0.01	13	317	15	0.03	<5	2	33	<5	0.09	<10	<10	68	<10	68	3
4579	0.9	2.26	9	59	<0.5	<5	0.05	<1	5	32	7	3.31	<1	0.04	<10	0.39	230	<2	0.01	14	551	13	0.05	<5	2	6	<5	0.04	<10	<10	79	<10	44	1
4599	<0.2	2.02	6	66	<0.5	<5	0.11	<1	17	18	10	5.79	<1	0.05	<10	0.49	827	<2	0.02	12	737	20	0.08	<5	1	9	<5	0.09	<10	<10	72	<10	70	3
4622	0.4	0.67	<5	52	<0.5	<5	0.08	<1	3	9	5	1.02	<1	0.07	10	0.09	100	<2	0.01	2	423	3	0.02	<5	<1	6	<5	0.02	<10	<10	34	<10	21	1
4644	0.4	1.80	7	39	<0.5	<5	0.04	<1	9	16	6	6.92	<1	0.05	12	0.22	781	2	0.02	4	780	38	0.07	<5	1	4	<5	0.16	<10	<10	62	<10	50	15
4666	0.6	1.34	<5	31	<0.5	<5	0.03	<1	7	14	1	4.27	<1	0.05	20	0.07	182	3	0.03	1	715	35	0.08	<5	1	2	<5	0.16	<10	<10	36	<10	39	65
4686	0.4	1.81	<5	165	<0.5	<5	0.23	<1	23	7	20	4.27	<1	0.06	<10	0.70	2446	<2	0.02	6	852	28	0.03	<5	2	11	<5	0.14	<10	<10	54	<10	95	2
4703	0.4	2.69	6	343	<0.5	<5	0.53	<1	20	13	9	4.80	<1	0.08	<10	1.07	1288	<2	0.01	6	808	34	0.08	<5	2	21	<5	0.13	<10	<10	53	<10	125	3
4727	0.2	1.35	14	98	<0.5	<5	0.35	<1	22	13	26	4.75	<1	0.08	<10	0.63	988	<2	0.01	12	1086	26	0.09	<5	1	10	<5	0.11	<10	<10	30	<10	94	2
4743	0.3	1.62	14	74	<0.5	<5	0.03	<1	17	40	9	4.82	<1	0.06	14	0.62	724	<2	0.01	37	848	18	0.05	<5	2	3	<5	0.01	<10	<10	36	<10	88	3
4760	0.6	1.81	10	115	<0.5	<5	0.07	<1	43	12	14	6.70	<1	0.07	10	0.20	4934	<2	0.02	2	2197	37	0.10	<5	1	4	<5	0.01	<10	19	70	<10	53	2
4781	0.2	1.69	15	75	<0.5	<5	0.03	<1	14	41	16	4.83	<1	0.05	14	0.71	453	<2	0.01	42	629	19	0.03	<5	2	4	<5	0.01	<10	<10	38	<10	91	3
4805	<0.2	1.19	10	61	<0.5	<5	0.07	<1	14	30	15	4.18	<1	0.04	10	0.47	724	<2	0.01	29	1169	14	0.06	<5	2	5	<5	0.01	<10	<10	30	<10	69	2
4830	<0.2	2.45	48	435	<0.5	<5	0.38	1	20	29	14	3.94	<1	0.06	<10	0.59	2151	3	0.02	28	774	14	0.06	<5	2	36	<5	0.06	<10	<10	52	<10	107	2
4847	<0.2	2.95	106	268	<0.5	<5	0.10	2	13	26	10	4.20	<1	0.06	12	0.50	3727	3	0.01	15	1668	18	0.16	<5	1	9	<5	0.06	<10	13	61	<10	119	2
4865	<0.2	1.81	10	86	<0.5	<5	0.41	<1	6	43	11	3.33	<1	0.05	<10	0.65	267	<2	0.01	39	780	10	0.04	<5	1	26	<5	0.02	<10	<10	36	<10	67	3
4890	<0.2	1.94	16	161	<0.5	<5	0.32	<1	23	39	21	4.69	<1	0.12	12	0.68	2150	<2	0.02	49	932	26	0.06	<5	2	20	<5	0.02	<10	<10	42	<10	166	3
4902	<0.2	0.65	<5	76	<0.5	<5	0.03	<1	4	3	2	0.45	<1	0.07	<10	0.04	26	<2	0.01	<1	229	9	0.02	<5	1	7	<5	0.07	<10	<10	31	<10	8	<1
4916	<0.2	1.33	9	119	<0.5	<5	0.08	<1	4	40	8	3.07	<1	0.08	12	0.51	97	<2	0.01	35	700	19	0.03	<5	2	7	<5	0.01	<10	<10	35	<10	55	2
4936	<0.2	0.90	6	64	<0.5	<5	0.07	<1	4	24	9	2.18	<1	0.06	10	0.28	90	<2	0.01	18	701	12	0.04	<5	1	6	<5	0.02	<10	<10	25	<10	38	1
1979	4.7	3.20	1076	29	<0.5	<5	0.06	20	12	9	36	6.07	<1	0.06	47	0.11	1738	2	0.03	<1	788	76	0.10	8	3	<1	<5	0.08	<10	<10	17	<10	154	41
2006	2.7	1.95	32	34	<0.5	<5	0.05	<1	7	15	14	3.43	<1	0.05	12	0.17	426	3	0.01	4	1103	23	0.12	<5	1	5	<5	0.07	<10	<10	57	<10	48	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2892SJ

Date : Sep-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment17

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
2023	18.9	1.64	260	109	<0.5	<5	0.03	4	6	2	24	4.48	1	0.06	11	0.14	1042	<2	0.01	<1	1071	39	0.06	<5	3	2	<5	0.01	<10	<10	144	<10	40	2
2072	0.5	1.07	67	59	<0.5	<5	0.02	1	4	2	7	1.08	<1	0.07	15	0.06	85	<2	0.01	1	524	7	0.04	<5	1	2	<5	0.01	<10	<10	19	<10	21	1
2094	2.8	1.74	2050	83	<0.5	<5	0.20	38	14	4	10	4.45	<1	0.09	27	0.31	2133	<2	0.01	<1	1376	57	0.08	6	1	5	<5	0.01	<10	<10	20	<10	164	3
2136	0.6	1.57	600	59	<0.5	5	0.03	10	35	3	36	7.60	<1	0.12	15	0.35	5009	<2	0.01	1	2419	121	0.07	<5	1	1	<5	0.01	<10	19	45	<10	114	3
2152	1.9	1.39	256	216	<0.5	5	0.08	5	40	6	19	4.95	<1	0.12	<10	0.19	8190	2	0.01	4	2140	85	0.14	<5	<1	5	<5	0.01	<10	35	56	<10	107	<1
2180	3.0	1.79	582	73	<0.5	<5	0.16	10	18	21	30	6.33	<1	0.10	10	0.58	1482	<2	0.01	4	2222	99	0.12	<5	1	6	<5	0.01	<10	<10	72	<10	177	3
2209	0.9	1.61	121	88	<0.5	<5	0.07	2	6	17	15	2.73	<1	0.05	<10	0.21	274	<2	0.01	3	596	14	0.06	<5	1	3	<5	0.03	<10	<10	80	<10	26	1
2233	1.0	1.35	68	63	<0.5	<5	0.03	1	4	16	16	2.60	<1	0.08	<10	0.12	149	<2	0.01	1	984	22	0.08	<5	1	1	<5	0.05	<10	<10	88	<10	19	1
2256	0.7	1.40	839	65	<0.5	<5	0.14	15	12	13	5	5.66	<1	0.08	17	0.14	1947	4	0.02	5	1164	42	0.11	<5	1	7	<5	0.09	<10	<10	52	<10	98	5
2281	1.1	2.30	49	43	<0.5	<5	0.06	<1	11	28	13	4.58	<1	0.05	10	0.30	577	2	0.01	10	850	34	0.09	<5	2	5	<5	0.10	<10	<10	66	<10	48	5
2300	0.4	1.31	46	56	<0.5	<5	0.04	1	3	6	5	1.13	<1	0.05	<10	0.07	53	<2	0.01	2	692	25	0.07	<5	<1	3	<5	0.03	<10	<10	47	<10	18	1
2332	<0.2	1.49	1092	47	<0.5	<5	0.02	20	14	3	19	7.67	<1	0.07	<10	0.13	995	<2	0.01	<1	628	90	0.05	<5	1	1	<5	0.08	<10	<10	48	<10	47	3
2362	<0.2	0.78	6	43	<0.5	<5	0.06	<1	15	20	7	1.35	1	0.04	<10	0.07	56	4	0.01	3	719	47	0.08	6	1	7	<5	0.34	<10	<10	101	<10	21	7
2387	0.6	1.64	93	139	<0.5	<5	0.12	1	21	6	22	5.21	<1	0.08	<10	0.36	2372	<2	0.01	3	934	38	0.22	<5	1	6	<5	0.04	<10	<10	87	<10	74	2
2405	3.8	2.26	1173	105	<0.5	6	0.12	22	46	2	155	10.30	<1	0.11	12	0.54	4495	<2	0.01	2	1528	198	0.17	<5	4	3	<5	0.01	<10	20	75	<10	180	4
2425	1.4	2.32	202	87	<0.5	<5	0.18	3	30	3	53	6.23	<1	0.13	11	0.64	3672	2	0.01	2	1258	137	0.16	<5	3	5	<5	0.01	<10	13	60	<10	190	3
2451	6.7	2.25	596	230	1.5	17	0.06	14	60	4	212	8.74	<1	0.10	27	0.34	8975	8	0.01	4	2331	377	0.16	<5	7	1	<5	0.01	<10	44	43	<10	556	4
2469	4.2	2.20	874	61	<0.5	<5	0.18	15	32	9	52	6.42	<1	0.10	15	0.31	3115	2	0.01	5	1041	71	0.05	<5	2	2	<5	0.02	<10	<10	54	<10	117	3
2489	5.8	2.41	745	64	<0.5	<5	0.07	13	28	6	70	7.76	<1	0.10	12	0.21	2774	<2	0.01	2	1262	78	0.06	<5	2	1	<5	0.01	<10	<10	75	<10	99	6
2494	5.7	2.43	653	58	<0.5	5	0.01	11	34	4	77	8.41	<1	0.09	10	0.24	3390	<2	0.01	<1	1382	69	0.05	<5	3	1	<5	0.01	<10	13	80	<10	76	4
2524	7.6	1.90	442	62	<0.5	<5	0.03	8	26	7	40	6.34	<1	0.07	10	0.27	2528	<2	0.01	2	1114	56	0.07	<5	2	2	<5	0.01	<10	<10	61	<10	66	3
2552	3.4	1.38	325	51	<0.5	<5	0.03	6	6	8	12	3.25	<1	0.07	17	0.13	613	<2	0.01	2	1093	66	0.07	<5	<1	3	<5	0.02	<10	<10	44	<10	61	1
2578	0.5	0.83	26	54	<0.5	<5	0.05	1	4	6	7	1.10	<1	0.05	10	0.08	90	<2	0.01	1	460	45	0.04	<5	1	6	<5	0.04	<10	<10	31	<10	26	1
2644	154.5	0.32	1751	45	0.5	<5	0.06	35	15	<1	210	7.29	<1	0.11	19	0.02	2146	<2	0.01	<1	1602	5256	0.11	78	2	<1	<5	<0.01	<10	<10	6	<10	1029	3
2667	2.7	1.70	557	72	<0.5	<5	0.01	10	16	10	57	10.72	<1	0.07	11	0.19	2212	<2	0.01	<1	3183	126	0.06	<5	1	2	<5	0.06	<10	12	103	<10	102	5
2692	4.9	2.00	216	73	<0.5	<5	0.08	4	20	12	55	5.99	<1	0.11	20	0.37	2721	2	0.01	6	2136	385	0.06	<5	2	4	<5	0.05	<10	<10	46	<10	263	4
2717	0.3	2.02	32	45	<0.5	<5	0.05	<1	10	14	17	5.90	<1	0.04	10	0.29	351	<2	0.01	6	580	42	0.04	<5	2	8	<5	0.11	<10	<10	84	<10	69	4
2743	<0.2	0.53	62	35	<0.5	<5	0.03	1	5	3	10	2.09	<1	0.09	13	0.07	269	<2	0.01	1	486	16	0.02	<5	1	4	<5	0.02	<10	<10	28	<10	49	1
2771	0.4	1.08	53	45	<0.5	<5	0.05	1	7	8	10	3.54	<1	0.06	11	0.16	530	2	0.01	3	799	29	0.02	<5	1	7	<5	0.05	<10	<10	59	<10	52	1
2792	5.0	1.46	159	75	<0.5	<5	0.04	2	13	14	19	5.84	<1	0.06	11	0.25	1238	2	0.01	7	1279	88	0.04	<5	1	3	<5	0.01	<10	<10	31	<10	83	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2892SJ

Date : Sep-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment17

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
2815	1.3	0.88	159	88	<0.5	<5	0.02	2	10	6	23	4.94	<1	0.07	11	0.19	565	3	0.01	3	1154	51	0.03	<5	2	3	<5	0.01	<10	<10	43	<10	99	2
2827	5.0	2.22	771	76	<0.5	<5	0.03	13	8	6	49	9.58	<1	0.07	<10	0.26	836	3	0.01	<1	3176	141	0.05	<5	2	3	<5	0.02	<10	<10	85	<10	91	5
2856	5.4	1.25	332	111	<0.5	<5	0.10	6	22	10	47	5.82	<1	0.08	15	0.48	2456	<2	0.01	10	1010	127	0.13	<5	2	6	<5	0.02	<10	<10	39	<10	188	4
2883	2.3	2.61	38	92	<0.5	<5	0.02	<1	21	69	53	8.21	<1	0.08	12	0.54	2692	3	0.01	7	2016	42	0.06	<5	4	2	<5	0.02	<10	<10	210	<10	163	4
2908	0.7	2.62	9	123	<0.5	<5	0.20	<1	15	36	24	5.22	<1	0.04	24	0.49	1733	3	0.01	21	1460	44	0.09	<5	2	13	<5	0.04	<10	<10	46	<10	118	5
2932	1.3	1.24	55	91	<0.5	<5	0.11	1	34	95	34	6.73	<1	0.07	<10	0.17	3143	9	0.01	7	2398	67	0.09	<5	2	9	<5	0.11	<10	<10	275	<10	85	3
2963	4.2	3.47	969	106	<0.5	<5	0.16	20	21	34	74	8.88	<1	0.04	56	0.17	7183	46	0.02	4	1876	258	0.20	5	4	<1	<5	0.04	<10	28	57	<10	398	27
2988	5.9	2.71	209	131	<0.5	<5	0.62	8	21	39	79	5.54	<1	0.06	28	0.42	5642	64	0.02	15	1700	60	0.15	<5	2	21	<5	0.04	<10	20	71	<10	386	5
3014	1.5	2.76	121	184	<0.5	<5	0.73	13	34	43	138	6.48	<1	0.06	18	0.82	4640	65	0.02	16	1452	104	0.15	<5	7	24	<5	0.06	<10	14	126	10	988	5
3042	4.3	3.42	37	198	<0.5	<5	0.61	7	32	41	124	5.50	<1	0.05	42	0.28	9450	74	0.03	15	2542	633	0.27	<5	3	15	<5	0.05	<10	43	66	<10	675	11
3066	4.6	2.18	24	27	<0.5	<5	0.04	<1	8	20	25	7.48	<1	0.04	21	0.11	544	14	0.03	3	1075	358	0.07	<5	2	2	<5	0.13	<10	<10	47	<10	144	29
3090	2.7	1.70	53	80	<0.5	<5	0.03	1	9	67	36	8.50	<1	0.04	<10	0.13	349	60	0.02	4	1217	33	0.06	<5	2	4	<5	0.11	<10	<10	340	<10	50	5
3119	3.2	3.04	36	69	<0.5	<5	0.03	1	47	44	289	8.91	<1	0.05	<10	0.62	5433	40	0.03	5	2383	115	0.08	<5	24	2	<5	0.01	<10	18	164	<10	115	6
3144	<0.2	1.82	71	50	<0.5	<5	0.04	1	8	24	52	6.54	<1	0.03	<10	0.15	285	23	0.01	4	716	44	0.05	<5	3	7	<5	0.12	<10	<10	160	<10	67	5
3167	0.7	0.98	253	105	<0.5	<5	0.11	4	5	8	9	2.37	<1	0.03	<10	0.05	427	5	0.01	3	452	65	0.02	<5	<1	4	<5	0.02	<10	<10	58	<10	46	1
3186	<0.2	1.10	118	51	<0.5	<5	0.03	2	5	7	16	3.91	<1	0.05	<10	0.09	429	5	0.01	2	799	113	0.03	<5	1	2	<5	0.02	<10	<10	69	<10	49	2
3216	1.1	1.48	123	74	<0.5	<5	0.02	1	8	36	22	8.11	<1	0.03	<10	0.11	531	29	0.01	3	1105	63	0.04	<5	2	3	<5	0.06	<10	<10	246	<10	52	4
3239	4.5	1.97	543	82	<0.5	<5	0.04	8	21	43	37	8.91	<1	0.04	<10	0.23	1324	65	0.01	2	890	128	0.04	<5	5	5	<5	0.18	<10	<10	279	<10	105	5
3263	4.1	2.05	119	59	<0.5	<5	0.03	2	8	27	59	6.83	<1	0.04	10	0.13	343	33	0.01	7	734	189	0.04	<5	3	4	<5	0.08	<10	<10	127	<10	99	3
3280	4.9	2.63	428	47	<0.5	<5	0.06	7	12	19	178	9.93	<1	0.03	<10	0.52	689	45	0.01	<1	1049	525	0.05	<5	6	7	<5	0.10	<10	<10	194	<10	372	6
3308	13.2	2.03	152	53	<0.5	<5	0.10	3	15	23	87	4.99	<1	0.08	<10	0.27	2986	72	0.02	9	1828	171	0.15	<5	1	7	<5	0.03	<10	<10	84	<10	168	2
3326	3.0	1.76	59	44	<0.5	<5	0.04	1	11	23	26	6.80	<1	0.06	11	0.22	795	23	0.02	7	1776	52	0.06	<5	2	4	<5	0.13	<10	<10	110	<10	83	5
3353	4.3	3.17	119	79	<0.5	<5	0.04	2	19	43	76	10.31	<1	0.02	<10	0.28	1030	198	0.02	1	1082	188	0.10	<5	5	6	<5	0.20	<10	<10	196	<10	134	10
3377	<0.2	1.65	21	70	<0.5	<5	0.19	1	15	26	47	4.69	<1	0.05	17	0.83	797	2	0.01	23	958	137	0.02	<5	4	7	<5	0.03	<10	<10	45	<10	148	2
3399	0.7	0.96	25	42	<0.5	<5	0.01	1	2	5	8	1.47	<1	0.04	<10	0.05	117	2	0.01	1	638	37	0.02	<5	1	1	<5	0.02	<10	<10	34	<10	17	1
3419	5.7	3.55	2470	56	<0.5	<5	0.04	40	22	23	46	6.62	<1	0.06	13	0.26	2848	10	0.01	2	1751	1043	0.09	<5	2	<1	<5	0.01	<10	<10	51	<10	560	11
3433	25.6	2.84	3053	86	<0.5	<5	0.10	57	103	275	703	11.23	<1	0.02	11	1.39	>10000	66	0.01	34	2041	1229	0.04	<5	33	3	<5	0.05	<10	45	266	10	758	6
3455	7.4	2.70	697	83	<0.5	<5	0.05	13	51	72	184	12.42	<1	0.03	<10	0.60	6233	108	0.01	4	1635	255	0.09	<5	9	1	<5	0.14	<10	18	295	10	133	6
3469	13.8	1.87	580	237	<0.5	<5	0.04	12	59	44	128	8.94	<1	0.05	<10	0.34	>10000	93	0.01	8	2025	1031	0.11	<5	4	3	<5	0.08	<10	82	228	<10	225	3
3486	34.4	2.11	701	90	<0.5	<5	0.06	13	89	37	214	9.29	<1	0.08	<10	0.51	>10000	84	0.02	7	2640	1018	0.15	<5	3	4	<5	0.04	<10	40	204	<10	246	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2892SJ

Date : Sep-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment17

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
3515	12.0	1.71	726	203	<0.5	<5	0.68	30	64	12	350	9.03	<1	0.10	20	0.37	9506	92	0.03	7	2116	1535	0.12	<5	3	18	<5	0.01	<10	36	68	13	1160	5
3534	7.8	2.69	869	121	<0.5	<5	0.03	15	43	46	177	8.56	<1	0.05	11	0.50	9412	95	0.01	7	1698	342	0.10	<5	7	1	<5	0.07	<10	35	261	12	359	3
3567	4.3	1.92	136	57	<0.5	<5	0.04	2	25	7	50	7.48	<1	0.07	<10	0.28	7786	31	0.02	3	3392	302	0.09	<5	1	6	<5	0.03	<10	27	89	<10	98	3
3590	12.2	1.81	627	54	<0.5	5	0.06	18	56	3	377	10.90	<1	0.08	<10	0.21	8596	67	0.03	1	2677	3118	0.16	<5	4	1	<5	0.01	<10	31	37	<10	674	6
3617	5.4	1.07	358	179	<0.5	<5	0.22	9	11	4	135	5.56	<1	0.06	10	0.15	4274	94	0.01	1	1748	831	0.05	<5	2	6	<5	0.01	<10	12	25	<10	513	4
3639	11.4	1.58	228	184	<0.5	<5	0.22	30	34	44	183	6.61	<1	0.07	<10	0.23	>10000	449	0.02	15	2630	9414	0.21	<5	1	9	<5	0.06	<10	73	87	11	1030	3
3659	1.2	1.00	326	120	<0.5	<5	0.02	5	14	3	65	7.46	<1	0.05	<10	0.06	581	38	0.02	1	1407	115	0.05	<5	1	2	<5	0.03	<10	<10	167	<10	132	3
3685	2.9	1.18	57	56	<0.5	<5	0.04	1	6	6	20	3.94	<1	0.05	<10	0.27	810	28	0.01	3	929	163	0.05	<5	<1	3	<5	0.03	<10	<10	56	<10	108	2
3712	2.6	1.04	110	63	<0.5	<5	0.03	2	7	4	31	4.54	<1	0.07	<10	0.10	858	43	0.01	1	1568	73	0.08	<5	<1	2	<5	0.02	<10	<10	60	<10	51	2
3736	12.7	2.94	204	165	<0.5	<5	0.76	18	43	16	1583	7.59	<1	0.13	117	0.49	5714	56	0.02	9	3167	1866	0.31	<5	16	21	<5	0.03	<10	19	50	13	1615	13
3759	3.8	1.21	259	169	<0.5	<5	0.06	6	39	4	53	8.13	<1	0.09	<10	0.12	8920	75	0.01	2	3835	705	0.12	<5	1	3	<5	0.01	<10	32	60	<10	524	5
3786	9.3	1.99	709	137	<0.5	5	0.03	24	93	4	460	12.56	<1	0.08	11	0.45	>10000	186	0.01	3	2907	2128	0.11	<5	13	<1	5	0.02	<10	55	57	12	1050	7
3813	4.3	3.00	115	104	<0.5	<5	0.51	6	63	10	704	6.12	<1	0.07	68	0.29	5404	61	0.01	5	1775	1989	0.15	<5	2	20	<5	0.02	<10	17	63	<10	616	3
3839	2.5	2.61	22	28	<0.5	<5	0.06	<1	5	18	101	5.62	<1	0.05	27	0.05	250	48	0.03	<1	813	383	0.11	<5	1	<1	<5	0.13	<10	<10	32	<10	80	204
3866	2.5	1.62	89	165	<0.5	<5	0.04	2	20	8	61	8.73	<1	0.05	<10	0.16	2147	118	0.01	3	1577	365	0.08	<5	1	4	<5	0.08	<10	<10	139	<10	143	4
3888	19.5	2.49	688	200	<0.5	13	0.01	97	55	10	453	14.83	<1	0.04	15	0.38	>10000	114	0.01	9	1972	5178	0.15	<5	53	<1	10	0.01	<10	165	54	24	2538	9
3916	4.8	1.50	827	67	<0.5	<5	0.03	14	48	1	284	11.67	<1	0.07	11	0.31	5246	54	0.01	<1	1878	455	0.09	<5	4	<1	<5	0.01	<10	15	35	<10	173	7
3940	5.4	0.95	1106	151	0.7	9	0.02	30	49	<1	209	13.45	<1	0.08	42	0.35	8752	24	0.01	3	3327	674	0.04	<5	8	<1	<5	<0.01	<10	29	23	<10	467	8
3961	3.2	2.56	590	75	<0.5	<5	0.04	11	76	<1	634	>15.00	<1	0.08	<10	0.98	6751	59	0.02	<1	4026	136	0.11	<5	10	<1	<5	0.05	<10	19	78	<10	237	9
3979	3.6	2.12	202	143	<0.5	<5	0.06	8	24	17	316	9.19	1	0.06	13	0.20	5507	177	0.02	5	1580	1809	0.08	<5	2	3	<5	0.04	<10	17	72	18	1912	4
3991	7.6	2.98	32	78	<0.5	<5	0.04	2	15	11	114	4.02	<1	0.08	10	0.21	1638	51	0.01	2	1396	56	0.09	<5	<1	2	<5	0.02	<10	<10	57	<10	261	2
4011	1.0	1.66	156	80	<0.5	<5	0.03	2	31	4	68	7.89	<1	0.11	15	0.51	3616	4	0.01	2	2016	280	0.04	<5	5	<1	<5	0.01	<10	<10	38	<10	333	8
4038	0.7	1.88	111	176	<0.5	<5	0.05	2	9	2	7	5.64	<1	0.08	<10	0.17	974	4	0.01	<1	1098	136	0.06	<5	1	2	<5	0.01	<10	<10	42	<10	165	5
4060	0.9	1.36	53	334	<0.5	<5	0.38	2	6	5	17	2.53	<1	0.10	<10	0.10	847	7	0.01	2	752	28	0.05	<5	<1	10	<5	0.03	<10	<10	53	<10	46	1
4079	0.5	1.68	79	118	<0.5	<5	0.15	2	18	8	36	5.18	<1	0.07	24	0.14	1884	14	0.02	1	955	69	0.06	<5	1	4	<5	0.08	<10	<10	58	<10	93	7
4101	0.7	2.82	50	89	<0.5	<5	0.07	1	12	14	31	5.50	<1	0.09	17	0.35	1198	3	0.02	8	1175	33	0.09	<5	1	2	<5	0.03	<10	<10	51	<10	82	4
4122	<0.2	2.53	49	43	<0.5	<5	0.05	<1	12	30	27	10.60	<1	0.06	25	0.16	1022	3	0.03	5	1233	92	0.12	<5	2	<1	<5	0.17	<10	<10	57	<10	99	86
4134	4.0	2.60	728	111	<0.5	<5	0.05	12	65	27	107	10.56	<1	0.07	17	0.88	8322	<2	0.01	29	2541	131	0.12	<5	7	1	<5	0.04	<10	28	72	<10	294	10
4155	<0.2	1.49	136	46	<0.5	<5	0.02	2	12	7	20	8.85	<1	0.06	<10	0.18	1000	<2	0.01	<1	1469	30	0.06	<5	1	1	<5	0.01	<10	<10	88	<10	37	6
4176	2.7	2.76	26	54	<0.5	<5	0.44	1	16	26	70	2.98	<1	0.05	38	0.25	984	4	0.03	14	766	41	0.13	<5	2	11	<5	0.11	<10	<10	27	<10	121	43

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2892SJ

Date : Sep-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment17

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
4196	0.2	2.34	350	34	<0.5	<5	0.03	5	25	10	47	11.75	<1	0.02	10	0.29	2784	<2	0.02	2	1383	38	0.11	<5	1	2	<5	0.04	<10	<10	53	<10	108	7
4214	0.7	2.27	156	58	<0.5	<5	0.04	2	17	25	27	10.47	<1	0.06	16	0.26	2815	3	0.02	6	1614	56	0.11	<5	1	3	<5	0.08	<10	<10	69	<10	97	12
4238	1.4	2.21	229	58	<0.5	<5	0.02	3	12	4	32	10.37	<1	0.04	<10	0.10	1241	<2	0.01	<1	1845	57	0.07	<5	1	1	<5	0.02	<10	<10	131	<10	50	5
4272	46.8	1.74	225	48	<0.5	<5	0.09	3	12	4	43	8.22	<1	0.03	10	0.46	756	3	0.01	2	971	559	0.07	<5	2	4	<5	0.01	<10	<10	54	<10	202	4
4289	8.5	1.88	177	43	<0.5	5	0.08	3	68	3	168	10.89	<1	0.04	17	0.97	3339	<2	0.01	6	2205	120	0.13	<5	5	1	<5	0.01	<10	<10	49	<10	207	5
4313	<0.2	1.40	13	41	<0.5	<5	0.05	<1	13	27	11	5.39	<1	0.03	11	0.43	380	3	0.01	19	542	25	0.05	<5	2	6	<5	0.17	<10	<10	83	<10	61	11
4325	<0.2	1.63	9	37	<0.5	<5	0.04	<1	10	29	10	7.84	<1	0.04	15	0.20	370	3	0.01	9	888	33	0.07	<5	1	3	<5	0.15	<10	<10	72	<10	63	20
4349	<0.2	2.32	16	83	<0.5	<5	0.23	<1	23	18	30	7.40	<1	0.07	13	0.30	1855	5	0.01	6	3044	36	0.23	<5	<1	7	<5	0.01	<10	<10	62	<10	79	3
4378	<0.2	1.59	6	68	<0.5	<5	0.17	<1	9	29	46	3.26	<1	0.06	<10	0.46	873	<2	0.01	26	1181	7	0.07	<5	<1	5	<5	0.01	<10	<10	33	<10	73	1
4391	0.9	0.69	<5	46	<0.5	<5	0.33	1	4	8	20	1.27	<1	0.06	<10	0.07	182	3	0.02	5	1427	45	0.11	<5	1	11	<5	0.02	<10	<10	16	<10	33	1
4417	<0.2	1.97	16	79	<0.5	<5	0.13	<1	12	33	19	5.80	<1	0.08	24	0.55	709	<2	0.02	26	1102	85	0.09	<5	2	7	<5	0.06	<10	<10	57	<10	96	4
4442	0.2	2.91	18	72	<0.5	<5	0.19	<1	10	22	25	5.05	<1	0.07	21	0.55	504	2	0.04	16	1229	23	0.10	<5	2	9	<5	0.09	<10	<10	47	<10	107	9
4466	<0.2	1.17	12	103	<0.5	<5	0.36	<1	16	46	34	3.93	<1	0.06	17	0.76	507	<2	0.01	67	1132	15	0.04	<5	3	22	<5	0.01	<10	<10	32	<10	143	2
4493	<0.2	1.19	12	80	<0.5	<5	0.20	<1	12	45	22	4.13	<1	0.06	21	0.71	431	<2	0.01	52	1166	14	0.02	<5	2	11	<5	0.01	<10	<10	35	<10	104	2
4511	0.4	0.61	<5	36	<0.5	<5	0.08	<1	6	8	8	1.57	<1	0.04	10	0.03	111	<2	0.01	3	384	21	0.05	<5	1	6	<5	0.10	<10	<10	60	<10	19	1
4563	0.2	0.91	<5	44	<0.5	<5	0.03	<1	6	20	16	1.52	<1	0.03	<10	0.06	87	2	0.01	9	536	16	0.06	<5	1	2	<5	0.05	<10	<10	55	<10	35	1
4597	<0.2	2.67	8	104	<0.5	<5	0.10	<1	10	17	26	7.44	<1	0.06	15	0.52	460	2	0.02	8	1397	35	0.09	<5	3	10	<5	0.12	<10	<10	56	<10	96	9
4613	<0.2	1.61	<5	47	<0.5	<5	0.07	<1	4	19	6	2.18	<1	0.03	14	0.06	78	3	0.01	3	526	20	0.06	<5	1	3	<5	0.06	<10	<10	50	<10	24	2
4637	<0.2	2.16	16	45	<0.5	<5	0.13	<1	19	27	13	5.39	<1	0.03	13	0.67	771	2	0.01	22	540	14	0.03	<5	3	10	<5	0.11	<10	<10	63	<10	97	12
4667	<0.2	1.53	8	38	<0.5	<5	0.09	<1	11	26	8	5.00	<1	0.03	<10	0.59	426	2	0.01	17	361	14	0.03	<5	2	12	<5	0.12	<10	<10	64	<10	67	5
4688	<0.2	1.31	<5	48	<0.5	<5	0.29	<1	25	65	17	4.28	1	0.06	<10	1.04	190	<2	0.04	36	759	16	0.04	<5	2	11	<5	0.33	<10	<10	120	<10	65	4
4711	<0.2	1.18	15	34	<0.5	<5	0.06	<1	10	25	18	5.80	<1	0.03	<10	0.11	141	<2	0.01	5	467	16	0.03	<5	2	8	<5	0.17	<10	<10	144	<10	41	3
4732	<0.2	3.01	12	33	<0.5	<5	0.08	<1	6	42	16	6.11	<1	0.04	<10	0.24	142	<2	0.02	9	1232	12	0.12	<5	1	8	<5	0.06	<10	<10	65	<10	40	4
4751	<0.2	1.74	10	81	<0.5	<5	0.18	<1	13	47	28	4.61	<1	0.03	<10	0.43	163	3	0.03	18	657	12	0.07	<5	2	26	<5	0.19	<10	<10	124	<10	47	3
4766	<0.2	0.52	<5	36	<0.5	<5	0.04	<1	7	17	5	1.15	1	0.04	<10	0.03	83	2	0.01	4	360	11	0.03	<5	1	3	<5	0.13	<10	<10	69	<10	20	1
4788	0.5	1.55	<5	45	<0.5	<5	0.05	<1	3	24	10	0.88	1	0.03	<10	0.08	39	2	0.01	6	1418	18	0.19	<5	<1	3	<5	0.05	<10	<10	27	<10	17	1
4815	<0.2	2.33	11	28	<0.5	<5	0.04	<1	8	22	7	8.86	<1	0.07	20	0.15	272	7	0.04	2	828	61	0.08	<5	1	1	<5	0.19	<10	<10	40	<10	74	125
4840	0.4	1.16	<5	46	<0.5	<5	0.07	<1	9	14	9	2.43	<1	0.04	12	0.17	177	3	0.02	6	612	29	0.08	<5	2	11	<5	0.18	<10	<10	76	<10	39	8
4861	<0.2	0.58	15	28	<0.5	<5	0.09	<1	8	11	9	2.46	<1	0.03	12	0.06	182	<2	0.01	6	236	7	0.02	<5	2	4	<5	0.09	<10	<10	109	<10	25	1
4881	<0.2	1.37	7	56	<0.5	<5	0.04	<1	6	36	6	2.67	<1	0.05	<10	0.33	163	<2	0.01	20	505	16	0.06	<5	1	6	<5	0.04	<10	<10	54	<10	35	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO#shipment17

Sample type:

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2892SJ

Date : Sep-04-08

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
4913	1.6	2.09	11	24	<0.5	<5	0.04	<1	8	18	9	7.73	<1	0.06	24	0.10	251	6	0.05	1	614	55	0.08	<5	2	<1	6	0.22	<10	<10	41	<10	75	317
4945	<0.2	1.41	32	52	<0.5	<5	0.13	<1	16	14	17	5.21	<1	0.06	<10	0.20	1264	6	0.02	3	1173	27	0.08	<5	1	6	<5	0.06	<10	<10	67	<10	45	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2936-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO# Shipment 18**
Attn: **Sue Deane**

Sep-04-08

We hereby certify the following assay of 22 core samples submitted Aug-18-08

Sample Name	Au g/tonne	Au-Check g/tonne
85493	0.08	0.08
85494	0.19	
85495	0.12	
85496	0.07	
85497	0.12	
85498	0.14	
85499	0.16	
85500	0.01	
120001	1.41	
120002	0.28	0.25
120003	0.18	
120004	0.38	
120005	1.65	
120006	0.13	
120007	0.22	
120008	0.69	
120009	0.49	
120010	0.22	
120011	3.76	
120012	0.32	0.28
120013	0.13	
120014	0.09	
*0218	0.91	
*BLANK	<0.01	

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2936-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO# Shipment 18**
Attn: **Sue Deane**

Sep-04-08

We hereby certify the following assay of 22 core samples submitted Aug-18-08

Sample Name	Au g/tonne	Au-Check g/tonne
120015	0.21	0.20
120016	0.20	
120017	0.18	
120018	<0.01	
120019	<0.01	
120020	0.15	
120021	0.11	
120022	0.08	
120023	0.19	
120024	0.10	0.08
120025	6.45	
120026	0.15	
120027	0.06	
120028	0.06	
120029	0.10	
120030	0.04	
120031	0.03	
120032	0.09	
120033	0.04	
120034	0.07	0.07
120035	0.06	
120036	0.06	
*0218	0.93	
*BLANK	<0.01	

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2936-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/PO# Shipment 18**
Attn: **Sue Deane**

Sep-04-08

We hereby certify the following assay of 22 core samples submitted Aug-18-08

Sample Name	Au g/tonne	Au-Check g/tonne
120037	0.13	0.12
120038	0.06	
120039	0.17	
120040	0.11	
120041	0.18	
120042	0.17	
120043	0.15	
120044	0.22	
120045	0.18	
139380	0.38	0.38
139381	0.59	
139382	0.32	
139383	0.62	
139384	0.83	
139385	0.74	
139386	1.05	
139387	0.42	
139388	5.21	
139389	0.26	
139390	0.31	0.28
139391	0.11	
139392	0.21	
*0218	0.92	
*BLANK	<0.01	

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-2936-RA4

Company: **Ascot Resources Ltd**
Project: Dilworth/PO# Shipment 18
Attn: Sue Deane

Sep-04-08

We hereby certify the following assay of 6 rock samples submitted Aug-18-08

Sample Name	Au g/tonne	Au-Check g/tonne
139393	0.19	0.16
139394	0.12	
139395	0.22	
139396	0.56	
139397	0.26	
*0218	0.90	
*BLANK	<0.01	

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2936RJ

Date : Sep-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO# Shipment 18

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
85493	1.4	1.77	74	109	<0.5	<5	4.69	22	30	168	70	5.59	<1	0.28	<10	0.87	1779	8	0.03	4	1204	14	0.87	<5	8	175	<5	0.02	<10	<10	106	<10	138	3
85494	1.1	1.67	152	85	<0.5	<5	4.72	20	36	121	69	5.28	<1	0.23	<10	0.86	2072	4	0.02	2	1073	21	1.59	<5	6	117	<5	0.02	<10	<10	98	<10	133	3
85495	0.9	1.77	85	107	<0.5	<5	2.97	21	27	118	72	5.42	<1	0.21	<10	0.97	1616	5	0.02	2	1163	50	1.19	<5	6	92	<5	0.02	<10	<10	118	<10	203	2
85496	1.0	2.48	81	105	<0.5	<5	3.05	22	26	88	72	6.19	<1	0.29	<10	1.66	2029	2	0.02	2	1184	55	1.09	<5	7	71	<5	0.02	<10	<10	126	<10	235	2
85497	2.8	2.07	55	106	<0.5	<5	3.10	20	31	151	72	5.93	<1	0.22	<10	1.35	1886	5	0.01	2	1059	659	1.50	<5	6	84	<5	0.02	<10	<10	108	23	2324	2
85498	1.4	1.55	69	94	<0.5	<5	3.12	15	50	46	72	4.69	<1	0.25	<10	0.99	2015	2	0.01	2	907	39	1.31	<5	5	88	<5	0.01	<10	<10	76	<10	149	2
85499	1.3	1.72	88	96	<0.5	<5	4.76	18	42	100	67	4.77	<1	0.22	<10	1.05	2356	3	0.01	2	937	50	1.03	<5	5	86	<5	0.01	<10	<10	97	<10	250	2
85500	<0.2	1.21	<5	302	<0.5	<5	0.66	11	130	3	76	2.50	<1	0.59	12	0.73	726	<2	0.10	6	814	4	0.01	<5	3	66	5	0.16	<10	<10	49	<10	69	2
120001	7.6	1.22	409	66	<0.5	<5	7.59	11	40	77	63	6.42	<1	0.13	<10	0.80	2659	2	0.01	<1	648	1330	>5.00	<5	4	148	<5	<0.01	<10	<10	63	43	4573	2
120002	4.2	1.59	179	106	<0.5	<5	2.91	19	61	121	72	5.97	<1	0.22	<10	0.88	2192	4	0.01	2	964	1385	2.22	<5	6	86	<5	<0.01	<10	<10	98	18	1977	2
120003	2.2	1.09	152	130	<0.5	<5	3.15	9	49	24	72	3.98	<1	0.20	<10	0.79	1737	2	0.01	1	814	597	1.49	<5	3	84	<5	<0.01	<10	<10	38	20	2194	2
120004	2.6	0.41	291	176	<0.5	<5	2.80	11	96	34	76	3.22	<1	0.32	<10	0.49	1556	3	0.01	2	788	207	2.09	<5	3	148	<5	<0.01	<10	<10	13	<10	682	2
120005	9.5	0.95	524	63	<0.5	<5	5.63	14	69	17	68	6.03	<1	0.12	<10	0.86	2716	5	0.01	1	496	69	4.78	<5	2	202	<5	<0.01	<10	<10	39	<10	83	2
120006	2.8	0.28	105	47	<0.5	<5	9.52	4	137	13	75	1.50	<1	0.13	<10	0.15	2469	<2	0.01	3	220	116	1.07	<5	1	204	<5	<0.01	<10	<10	9	<10	140	1
120007	1.1	0.96	216	116	<0.5	<5	5.40	6	41	5	64	2.67	<1	0.31	<10	0.50	1970	<2	0.01	1	679	44	1.13	<5	2	197	<5	<0.01	<10	<10	25	<10	83	2
120008	4.8	0.91	313	126	<0.5	<5	3.95	9	87	88	74	3.89	<1	0.24	<10	0.51	1698	2	0.01	6	633	859	2.75	<5	2	96	<5	<0.01	<10	<10	33	18	2057	3
120009	3.2	0.79	410	62	<0.5	<5	2.93	12	81	37	76	6.06	<1	0.17	<10	0.53	1589	3	0.01	1	713	335	>5.00	<5	2	70	<5	<0.01	<10	<10	45	<10	58	3
120010	0.8	1.11	99	75	<0.5	<5	2.62	11	39	48	51	3.63	<1	0.17	<10	0.54	1405	2	0.01	1	698	50	1.27	<5	3	68	<5	<0.01	<10	<10	51	<10	292	1
120011	9.1	0.84	523	66	<0.5	<5	4.04	13	68	308	74	6.75	<1	0.19	<10	0.49	1943	2	0.01	1	769	479	>5.00	<5	2	112	<5	<0.01	<10	<10	38	83	8768	3
120012	1.8	1.41	109	89	<0.5	<5	3.17	15	85	92	72	4.14	<1	0.27	<10	0.64	1415	4	0.02	2	912	612	0.82	<5	4	99	<5	<0.01	<10	<10	64	<10	193	2
120013	1.7	1.38	49	110	<0.5	<5	2.11	15	82	119	77	4.49	<1	0.26	<10	0.63	1207	3	0.02	2	949	247	0.60	<5	4	66	<5	<0.01	<10	<10	58	<10	326	2
120014	0.3	1.80	8	126	<0.5	<5	2.96	17	54	77	73	5.26	<1	0.21	10	1.00	1235	4	0.04	1	1023	35	0.43	<5	7	146	<5	0.01	<10	<10	103	<10	134	2
120015	1.3	1.83	21	74	<0.5	<5	2.80	<1	19	39	137	5.23	<1	0.20	<10	1.00	1267	6	0.03	2	1095	51	0.56	<5	6	114	<5	0.01	<10	<10	116	<10	110	3
120016	0.2	1.78	31	84	<0.5	<5	1.49	<1	20	42	30	4.82	1	0.27	<10	0.97	996	2	0.03	2	1153	14	0.51	<5	5	63	<5	<0.01	<10	<10	99	<10	98	2
120017	0.6	1.66	30	144	<0.5	<5	2.23	<1	18	46	128	4.81	<1	0.26	<10	0.93	1056	5	0.03	2	1058	20	0.63	<5	6	79	<5	0.01	<10	<10	104	<10	89	2
120018	<0.2	0.95	<5	468	<0.5	<5	2.50	<1	10	39	2	2.29	<1	0.33	16	0.63	792	<2	0.03	5	779	7	0.50	<5	3	145	<5	<0.01	<10	<10	25	<10	43	6
120019	0.3	0.48	6	1176	<0.5	<5	2.57	<1	9	38	12	1.98	<1	0.34	16	0.56	745	<2	0.03	5	739	16	0.28	<5	3	128	<5	<0.01	<10	<10	10	<10	45	4
120020	2.4	0.81	113	89	<0.5	<5	2.89	2	23	54	187	5.70	<1	0.31	<10	0.77	1186	6	0.01	2	949	127	3.94	<5	4	135	<5	<0.01	<10	<10	46	<10	155	3
120021	1.7	1.67	85	109	<0.5	<5	3.60	1	17	55	150	5.05	<1	0.33	<10	0.89	1647	5	0.02	3	1056	12	1.56	<5	5	124	<5	<0.01	<10	<10	79	<10	110	2
120022	1.9	1.61	91	89	<0.5	<5	3.92	1	22	41	186	5.40	<1	0.24	<10	0.84	1687	7	0.02	2	1166	14	1.87	<5	6	130	<5	<0.01	<10	<10	100	<10	109	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V2936RJ

Date : Sep-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO# Shipment 18

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120023	1.6	1.84	207	103	<0.5	<5	3.58	3	19	47	172	5.46	<1	0.30	<10	0.97	1678	7	0.03	3	988	16	0.90	<5	6	129	<5	0.01	<10	<10	101	<10	111	3
120024	2.3	1.19	63	119	0.5	<5	4.16	1	18	35	163	4.87	<1	0.45	<10	1.00	2089	8	0.01	3	1195	30	1.02	<5	6	285	<5	<0.01	<10	<10	32	<10	115	2
120025	3.4	1.76	691	235	<0.5	181	10.37	11	55	89	515	6.88	11	0.19	15	0.41	1100	118	0.05	82	988	96	2.86	<5	4	140	<5	0.13	<10	<10	53	39	116	18
120026	1.7	1.48	177	76	<0.5	<5	2.93	3	19	55	140	4.53	<1	0.26	<10	0.71	1230	9	0.02	3	870	36	0.76	<5	4	133	<5	<0.01	<10	<10	74	<10	120	2
120027	0.7	1.59	85	107	<0.5	<5	2.68	1	14	61	94	4.23	<1	0.27	<10	0.91	1133	4	0.02	3	947	7	0.58	<5	4	71	<5	0.01	<10	<10	75	<10	70	2
120028	0.4	1.41	12	175	<0.5	<5	3.20	<1	14	42	66	4.20	<1	0.24	<10	1.12	1300	3	0.03	2	976	5	0.27	<5	6	190	<5	0.05	<10	<10	69	<10	81	3
120029	<0.2	1.66	13	164	<0.5	<5	2.82	<1	16	56	74	4.47	<1	0.15	<10	1.25	1017	4	0.03	2	886	4	0.42	<5	5	148	<5	0.06	<10	<10	76	<10	85	3
120030	0.4	1.38	10	129	<0.5	<5	2.92	<1	11	52	68	3.90	<1	0.29	<10	0.92	1003	2	0.04	2	959	5	0.33	<5	5	136	<5	<0.01	<10	<10	59	<10	72	2
120031	0.4	0.97	36	97	<0.5	<5	2.87	<1	11	65	55	3.65	<1	0.29	<10	0.83	1056	3	0.02	2	840	4	0.51	<5	5	154	<5	<0.01	<10	<10	37	<10	48	2
120032	0.8	1.01	73	179	<0.5	<5	2.46	1	14	42	59	3.99	<1	0.36	<10	0.85	1264	5	0.01	2	970	11	0.76	<5	4	121	<5	<0.01	<10	<10	32	<10	63	2
120033	0.5	1.26	37	284	<0.5	<5	2.95	1	10	71	30	3.44	<1	0.25	<10	0.74	1126	3	0.02	3	835	7	0.54	<5	4	108	<5	<0.01	<10	<10	47	<10	87	2
120034	0.6	1.04	77	74	<0.5	<5	2.54	1	9	88	35	3.32	<1	0.23	<10	0.63	1069	6	0.01	3	709	5	0.94	<5	3	107	<5	<0.01	<10	<10	37	<10	47	2
120035	0.9	1.33	96	87	<0.5	<5	3.02	1	13	57	51	4.04	<1	0.26	<10	0.81	1148	3	0.02	3	907	18	1.06	<5	4	112	<5	<0.01	<10	<10	56	<10	64	2
120036	0.4	1.64	51	88	<0.5	<5	2.28	1	16	55	57	4.58	<1	0.32	<10	1.05	1124	5	0.02	4	1046	7	1.25	<5	4	69	<5	<0.01	<10	<10	63	<10	90	2
120037	0.6	1.23	141	103	<0.5	<5	4.11	2	14	84	49	4.79	<1	0.23	<10	1.05	1690	5	0.01	3	1150	12	2.36	<5	3	87	<5	<0.01	<10	<10	52	<10	60	2
120038	8.0	1.70	312	132	<0.5	<5	0.63	5	14	64	24	7.23	1	0.23	<10	1.35	1290	<2	0.01	2	1798	101	2.80	10	4	6	<5	<0.01	<10	<10	65	<10	199	3
120039	0.5	0.76	61	230	0.6	<5	2.85	1	12	99	50	3.90	<1	0.27	<10	0.82	1346	7	0.01	4	1089	7	1.11	<5	3	77	<5	<0.01	<10	<10	28	<10	58	2
120040	0.8	0.44	191	68	0.6	<5	3.60	3	13	122	21	3.24	<1	0.27	<10	0.43	1228	4	0.01	4	904	17	1.97	<5	2	79	<5	<0.01	<10	<10	12	<10	64	2
120041	2.3	1.84	34	167	<0.5	<5	5.73	2	20	27	162	5.88	<1	0.36	<10	1.18	2736	8	0.01	1	1573	13	1.41	<5	5	160	<5	<0.01	<10	<10	73	<10	271	2
120042	3.5	2.05	21	173	<0.5	<5	5.52	1	23	16	233	6.33	<1	0.35	<10	1.40	2715	13	0.01	1	1590	14	0.90	<5	4	183	<5	<0.01	<10	<10	73	<10	278	3
120043	2.7	1.43	53	167	0.5	<5	3.30	2	16	18	208	5.67	<1	0.33	<10	0.78	1890	6	0.01	1	1489	14	0.79	<5	3	78	<5	<0.01	<10	<10	40	<10	260	2
120044	3.6	1.26	79	115	0.5	<5	5.54	2	19	16	278	5.35	<1	0.31	<10	0.91	2199	66	0.01	1	1456	16	2.38	<5	3	147	<5	<0.01	<10	<10	41	<10	239	2
120045	3.9	1.84	22	143	0.5	<5	4.02	1	20	19	381	5.43	<1	0.35	<10	1.07	2123	64	0.01	1	1438	19	0.91	<5	3	113	<5	<0.01	<10	<10	61	<10	282	2
139380	6.6	1.15	389	117	<0.5	<5	0.27	7	20	48	26	4.78	<1	0.23	<10	0.69	1640	<2	0.01	3	1472	79	1.58	<5	3	4	<5	<0.01	<10	<10	51	<10	68	4
139381	102.0	1.47	1307	155	<0.5	<5	0.34	22	38	25	55	5.87	<1	0.33	<10	0.79	1150	<2	0.01	6	1750	141	2.23	21	4	6	<5	<0.01	<10	<10	74	<10	73	3
139382	2.8	1.53	2021	178	<0.5	<5	0.39	36	41	35	39	5.30	<1	0.26	10	0.80	1156	<2	0.01	7	1892	28	1.15	15	4	8	<5	<0.01	<10	<10	77	<10	74	3
139383	8.8	0.60	2184	153	<0.5	<5	0.18	38	10	94	54	3.37	<1	0.24	<10	0.20	372	<2	0.01	3	942	154	1.78	19	1	4	<5	<0.01	<10	<10	21	<10	273	2
139384	31.7	0.48	846	145	<0.5	<5	0.25	27	9	150	74	3.16	<1	0.18	<10	0.18	519	<2	0.01	4	742	1157	2.02	10	1	6	<5	<0.01	<10	<10	17	16	1980	2
139385	48.7	0.23	283	112	<0.5	<5	0.02	5	1	154	8	2.38	<1	0.17	<10	0.02	42	<2	0.01	2	475	51	0.10	8	1	2	<5	<0.01	<10	<10	8	<10	25	1
139386	10.9	0.29	462	164	<0.5	<5	0.01	8	2	114	9	3.63	<1	0.24	<10	0.02	52	2	0.01	1	793	63	0.15	16	2	2	<5	<0.01	<10	<10	11	<10	67	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/PO# Shipment 18

Sample type:

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V2936RJ**

Date : Sep-04-08

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139387	24.6	0.29	494	153	<0.5	<5	0.01	8	2	110	12	4.11	1	0.24	<10	0.02	28	<2	0.01	1	941	120	0.87	20	1	3	<5	<0.01	<10	<10	13	<10	32	2
139388	23.8	0.25	290	133	<0.5	<5	0.01	5	2	135	11	3.43	<1	0.22	<10	0.02	24	<2	0.01	2	762	81	0.63	11	1	3	<5	<0.01	<10	<10	10	<10	38	2
139389	156.3	0.25	354	142	<0.5	<5	0.01	8	2	170	22	4.95	1	0.20	<10	0.02	148	<2	0.01	2	847	294	0.52	20	1	5	<5	<0.01	<10	<10	11	<10	462	2
139390	45.4	0.21	217	125	<0.5	<5	0.02	3	3	181	25	5.06	<1	0.18	<10	0.02	91	<2	0.01	3	1099	67	0.90	11	1	7	<5	<0.01	<10	<10	9	<10	35	2
139391	2.7	1.55	195	289	0.5	<5	0.49	3	11	48	22	6.49	1	0.25	<10	1.06	1160	<2	0.02	2	1612	61	0.91	5	4	9	<5	<0.01	<10	<10	62	<10	151	4
139392	3.3	1.18	273	115	<0.5	<5	0.13	4	5	66	13	5.73	1	0.18	<10	0.82	927	<2	0.01	1	1491	63	0.91	7	3	2	<5	<0.01	<10	<10	55	<10	82	3
139393	9.3	1.79	160	140	<0.5	<5	0.17	2	11	44	12	6.82	<1	0.32	<10	1.09	1094	<2	0.01	<1	1343	108	1.98	11	4	5	<5	<0.01	<10	<10	67	<10	105	5
139394	8.0	1.75	260	111	<0.5	<5	0.49	2	12	52	17	5.95	1	0.25	<10	1.15	1023	<2	0.01	1	1504	79	2.02	14	4	8	<5	<0.01	<10	<10	62	<10	144	5
139395	2.8	0.68	241	118	<0.5	<5	0.07	2	6	45	6	5.30	1	0.28	<10	0.25	304	<2	0.01	<1	1291	31	0.76	9	2	4	<5	<0.01	<10	<10	34	<10	35	4
139396	36.8	0.28	376	183	<0.5	<5	0.04	4	4	165	61	2.77	<1	0.26	<10	0.05	143	<2	0.01	3	514	963	0.99	20	1	13	<5	<0.01	<10	<10	14	<10	477	2
139397	8.7	0.75	304	172	<0.5	<5	0.16	3	7	67	41	3.73	<1	0.33	<10	0.27	455	<2	0.01	2	1067	162	1.54	12	2	8	<5	<0.01	<10	<10	34	<10	209	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Quality Assaying for over 25 Years

Assay Certificate

8V-3008-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 19**
Attn: **Sue Deane**

Sep-04-08

We hereby certify the following assay of 22 rock samples submitted Aug-21-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
SD08-15	0.03	<0.01	<0.1	
SD08-16	0.03		<0.1	
SD08-17	0.02		<0.1	
SD08-18	0.03		<0.1	
139398	0.41		4.6	
139399	0.54		>200	284.7
139400	0.62		193	
139401	0.25		10.6	
139402	0.30		5.7	
139403	0.29	0.27	8.6	
139404	0.50		6.7	
139405	0.33		9.1	
139406	0.32		21.2	
139407	1.46		24.0	
139408	0.25		4.3	
139409	0.15		8.2	
139410	0.27		12.3	
139411	0.23		23.8	
139412	0.20		7.5	
139413	0.25	0.29	7.7	
139414	0.21		5.3	
139415	0.34		5.6	
*0218	0.92			
*CCu-1c				129.7
*BLANK	<0.01			<0.1

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3008-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 19**
Attn: **Sue Deane**

Sep-04-08

We hereby certify the following assay of 22 rock samples submitted Aug-21-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %	Zn %
139416	0.12	0.10	8.2		
139417	0.12		6.9		
139418	0.13		16.2	1.06	1.51
139419	0.12		8.5		
139420	0.11		8.7		
139421	0.11		12.0		
139422	0.17		10.0		
139423	0.21		17.6		
139424	0.05		6.5		
139425	0.13	0.13	18.3		
139426	0.33		36.1	1.54	
139427	0.47		25.6		
139428	0.08		4.2		
139429	0.06		2.9		
139430	0.11		21.4	1.01	
139431	0.24		2.9		
139432	0.17		10.9		
139433	0.33		38.0	1.38	
139451	0.04		1.9		
139452	0.02	0.01	1.5		
139453	0.04		2.0		
139454	0.03		1.9		
*0218	0.91				
*CCu-1c				0.34	3.96
*BLANK	<0.01			<0.01	<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3008-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 19**
Attn: **Sue Deane**

Sep-04-08

We hereby certify the following assay of 22 rock samples submitted Aug-21-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
139455	0.03	0.01	1.9
139456	0.04		2.1
139457	0.04		1.8
139458	0.03		1.3
139459	0.02		1.3
139460	0.01		1.6
139461	0.01		2.1
139462	0.04		2.5
139463	0.02		3.1
139464	0.01	0.02	2.1
139465	0.03		2.3
139466	0.04		2.7
139467	0.03		1.1
139468	0.02		1.4
139469	0.01		0.6
120046	0.04		0.2
120047	0.13		0.4
120048	0.07		0.4
120049	0.04		0.7
120050	<0.01	<0.01	<0.1
120051	0.08		0.7
120052	0.03		0.5
*0218	0.92		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3008-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 19**
Attn: **Sue Deane**

Sep-04-08

We hereby certify the following assay of 22 core samples submitted Aug-21-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120053	0.10	0.11	0.4
120054	0.12		3.4
120055	0.17		0.8
120056	0.08		0.3
120057	0.13		0.9
120058	0.06		0.5
120059	0.03		0.4
120060	0.07		<0.1
120061	0.03		<0.1
120062	0.32	0.39	0.9
120063	0.04		0.2
120064	0.08		0.6
120065	0.10		0.2
120066	0.27		0.6
120067	0.21		1.2
120068	0.32		2.4
120069	0.25		4.9
120070	0.21		1.5
120071	0.27		2.4
120072	0.16	0.17	4.0
120073	0.15		1.1
120074	0.14		6.3
*0218	0.92		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3008-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 19**
Attn: **Sue Deane**

Sep-04-08

We hereby certify the following assay of 22 core samples submitted Aug-21-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120075	1.82	NES	193
120076	0.26		1.0
120077	0.34		7.6
120078	0.33		2.8
120079	0.33		3.7
120080	0.03		0.7
120081	0.10		0.9
120082	0.07		1.7
120083	0.11		1.6
120084	0.76	0.85	14.4
120085	0.06		3.9
120086	0.04		0.1
120087	0.04		0.2
120088	0.09		0.2
120089	0.05		0.4
120090	0.04		1.3
120091	0.05		1.8
120092	0.03		0.3
120093	0.04		0.7
120094	0.07	0.06	0.4
120095	0.08		0.3
120096	0.03		0.9
*0218	0.91		
*CCu-1c			
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3008-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 19**
Attn: **Sue Deane**

Sep-04-08

We hereby certify the following assay of 22 core samples submitted Aug-21-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120097	0.04	0.04	0.7
120098	0.02		0.4
120099	0.03		0.7
120100	<0.01		<0.1
120101	0.05		0.6
120102	0.49		0.9
120103	0.31		0.7
120104	0.09		0.4
120105	0.03		1.0
120106	0.45	0.44	7.6
120107	1.22		2.9
120108	0.04		1.4
120109	0.04		1.3
120110	0.06		2.1
120111	0.10		6.9
120112	0.03		1.6
120113	0.04		2.4
120114	0.11		4.6
120115	0.31		0.3
120116	0.15	0.16	0.9
120117	0.10		0.3
*0218	0.91		
*BLANK	<0.01		

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3008RJ

Date : Sep-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 19

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
SD08-15	<0.2	0.25	<5	29	<0.5	<5	3.59	<1	6	161	20	2.54	<1	0.02	<10	0.92	668	<2	0.01	26	220	4	0.01	<5	3	469	<5	<0.01	<10	<10	8	<10	34	1
SD08-16	<0.2	0.28	<5	25	<0.5	<5	1.56	<1	3	125	5	1.32	<1	0.03	<10	0.80	389	2	0.01	23	373	14	0.02	<5	1	371	<5	<0.01	<10	<10	7	<10	23	1
SD08-17	<0.2	0.84	<5	16	<0.5	<5	0.10	<1	5	205	7	2.47	<1	0.02	<10	0.54	253	<2	0.01	38	379	4	0.01	<5	2	13	<5	<0.01	<10	<10	18	<10	47	1
SD08-18	<0.2	2.35	12	131	<0.5	<5	0.12	<1	8	100	19	4.22	<1	0.16	<10	1.50	457	<2	0.02	101	795	14	0.11	<5	4	12	<5	<0.01	<10	<10	62	<10	114	2
139398	4.6	0.27	465	215	<0.5	<5	0.03	8	2	120	2	2.41	<1	0.31	<10	0.03	41	<2	0.01	3	842	64	0.59	<5	1	10	<5	<0.01	<10	<10	9	<10	24	1
139399	>200.0	0.13	606	83	<0.5	<5	0.02	11	1	127	3	1.62	<1	0.16	<10	0.01	22	4	0.01	2	328	918	0.59	63	<1	6	<5	<0.01	<10	<10	5	<10	87	1
139400	193.7	0.16	1121	119	<0.5	<5	0.08	26	2	113	36	3.05	<1	0.24	<10	0.02	78	<2	0.01	2	725	1173	1.21	69	1	20	<5	<0.01	<10	<10	6	11	1213	1
139401	10.6	0.28	388	128	<0.5	<5	0.02	6	2	40	2	3.11	<1	0.28	<10	0.02	102	<2	0.01	<1	1076	60	0.20	11	1	6	<5	<0.01	<10	<10	9	<10	39	2
139402	5.7	0.22	386	79	<0.5	<5	0.03	6	2	33	6	4.53	<1	0.18	<10	0.01	137	<2	0.01	<1	1346	41	0.13	8	1	3	<5	<0.01	<10	<10	7	<10	38	2
139403	8.6	0.27	316	129	<0.5	<5	0.06	5	5	29	12	4.71	<1	0.24	<10	0.02	103	<2	0.01	<1	1701	32	1.15	12	1	5	<5	<0.01	<10	<10	7	<10	21	2
139404	6.7	0.27	221	193	<0.5	<5	0.02	4	2	137	2	2.49	<1	0.30	<10	0.02	51	<2	0.01	3	696	37	0.43	9	1	7	<5	<0.01	<10	<10	8	<10	18	1
139405	9.1	0.27	202	330	<0.5	<5	0.01	3	2	60	5	3.05	<1	0.36	<10	0.02	23	<2	0.01	<1	842	61	0.69	8	1	11	<5	<0.01	<10	<10	8	<10	51	1
139406	21.2	0.20	286	165	<0.5	<5	0.02	5	2	156	9	2.79	<1	0.21	<10	0.01	38	2	0.01	3	682	279	1.04	12	1	9	<5	<0.01	<10	<10	7	<10	83	1
139407	24.0	0.25	372	129	<0.5	<5	0.02	7	4	79	19	3.79	<1	0.24	<10	0.02	22	2	0.01	2	860	418	1.39	9	1	6	<5	<0.01	<10	<10	9	<10	131	2
139408	4.3	0.18	207	114	<0.5	<5	0.01	3	1	137	1	1.36	<1	0.19	<10	0.01	36	<2	0.01	3	330	107	0.23	5	1	4	<5	<0.01	<10	<10	7	<10	14	1
139409	8.2	0.25	354	254	<0.5	<5	0.01	6	1	63	<1	2.73	<1	0.28	<10	0.02	22	2	0.01	<1	871	356	0.47	9	1	10	<5	<0.01	<10	<10	9	<10	22	1
139410	12.3	0.21	587	124	<0.5	<5	0.01	10	1	122	<1	2.56	<1	0.23	<10	0.01	30	<2	0.01	2	847	887	0.48	13	1	12	<5	<0.01	<10	<10	7	<10	11	1
139411	23.8	0.21	162	199	<0.5	<5	0.01	3	2	88	9	1.96	<1	0.25	<10	0.01	63	2	0.01	1	521	469	0.52	9	1	10	<5	<0.01	<10	<10	6	<10	102	1
139412	7.5	0.27	219	189	<0.5	<5	0.03	4	4	68	12	2.85	<1	0.23	<10	0.02	70	<2	0.01	1	806	259	0.76	5	1	10	<5	<0.01	<10	<10	7	<10	142	1
139413	7.7	0.34	224	164	<0.5	<5	0.06	5	7	44	24	3.65	<1	0.25	<10	0.04	97	2	0.01	<1	919	274	1.70	<5	1	9	<5	<0.01	<10	<10	11	<10	276	2
139414	5.3	0.34	161	369	<0.5	<5	0.06	3	4	59	17	2.91	<1	0.22	<10	0.03	72	<2	0.01	1	868	279	1.11	<5	1	5	<5	<0.01	<10	<10	8	<10	120	1
139415	5.6	0.56	225	307	<0.5	<5	0.12	4	9	46	22	3.16	<1	0.30	<10	0.14	535	<2	0.01	1	981	136	0.82	<5	2	7	<5	<0.01	<10	<10	14	<10	160	2
139416	8.2	1.52	106	51	<0.5	<5	5.64	36	15	125	147	4.80	<1	0.17	<10	1.13	4061	14	0.01	15	764	4781	2.72	<5	5	92	<5	0.01	<10	14	59	65	6252	1
139417	6.9	1.47	91	66	<0.5	<5	2.29	23	16	189	54	4.98	<1	0.18	<10	1.07	4358	<2	0.01	20	848	4208	2.32	<5	6	38	<5	0.03	<10	15	64	49	4666	2
139418	16.2	1.68	123	57	<0.5	<5	1.66	70	21	197	121	6.77	1	0.20	<10	1.28	4640	<2	0.01	24	948	>10000	4.53	<5	7	47	<5	0.01	<10	18	70	171	>10000	2
139419	8.5	1.51	74	54	<0.5	<5	1.30	22	16	189	82	4.88	<1	0.15	<10	1.17	4907	<2	0.01	20	926	5320	1.89	<5	6	23	<5	0.01	<10	18	66	48	4943	1
139420	8.7	1.12	92	47	<0.5	<5	1.58	20	15	217	77	5.17	<1	0.13	<10	0.85	3543	<2	0.01	19	702	4953	3.01	<5	5	22	<5	<0.01	<10	13	50	41	4225	2
139421	12.0	1.94	109	50	<0.5	<5	3.83	43	23	189	236	6.10	<1	0.16	<10	1.65	4496	<2	0.01	27	906	6327	2.90	<5	9	83	<5	<0.01	<10	17	79	83	7980	2
139422	10.0	1.47	85	65	<0.5	<5	3.65	37	19	150	63	5.69	<1	0.21	<10	1.40	5249	<2	0.01	19	946	5954	3.19	<5	7	106	<5	<0.01	<10	21	51	73	7259	2
139423	17.6	0.56	99	62	<0.5	<5	2.11	32	15	127	220	5.20	<1	0.16	<10	0.57	3001	<2	0.01	15	701	6901	2.93	5	5	92	<5	<0.01	<10	12	23	67	6737	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3008RJ**

Date : Sep-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 19

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139424	6.5	1.90	50	80	<0.5	<5	3.70	25	18	110	80	4.86	<1	0.18	<10	1.62	4081	<2	0.01	14	914	3182	1.17	<5	8	89	<5	<0.01	<10	14	76	44	4423	1
139425	18.3	1.79	292	73	<0.5	<5	0.60	42	17	98	317	7.52	1	0.22	<10	0.94	2969	3	0.01	6	770	6325	2.72	<5	5	9	<5	0.01	<10	14	55	40	4172	3
139426	36.1	1.29	2116	47	<0.5	5	1.11	119	22	97	1081	10.76	1	0.18	<10	0.61	1973	<2	0.01	6	853	>10000	>5.00	9	4	19	<5	0.03	<10	15	48	91	9135	5
139427	25.6	1.68	7493	76	<0.5	<5	1.17	250	21	70	884	7.83	1	0.23	<10	0.91	2588	<2	0.01	7	863	8355	3.53	10	5	14	<5	0.03	<10	12	61	100	9600	3
139428	4.2	2.13	273	131	<0.5	<5	2.78	14	18	35	102	5.83	<1	0.28	<10	1.43	4013	2	0.01	4	1154	991	1.47	<5	5	35	<5	0.10	<10	14	74	16	1136	2
139429	2.9	0.64	137	148	<0.5	<5	0.10	5	6	116	68	2.67	<1	0.20	<10	0.28	2156	3	0.01	2	492	696	0.37	<5	1	3	<5	<0.01	<10	<10	15	<10	401	2
139430	21.4	0.52	224	162	<0.5	<5	0.31	28	6	119	283	3.15	<1	0.14	<10	0.27	1592	<2	0.01	3	444	>10000	1.44	8	1	6	<5	<0.01	<10	<10	15	31	3505	2
139431	2.9	0.54	258	139	<0.5	<5	0.29	11	5	87	61	4.34	<1	0.20	<10	0.29	1031	2	0.01	1	654	1341	1.81	<5	1	8	<5	<0.01	<10	<10	21	<10	895	3
139432	10.9	0.23	280	105	<0.5	<5	1.68	35	7	169	172	3.82	<1	0.14	<10	0.09	1666	<2	0.01	4	336	4720	2.03	<5	1	43	<5	<0.01	<10	<10	4	40	4073	2
139433	38.0	0.09	845	241	<0.5	<5	0.01	19	3	127	196	7.17	<1	0.19	<10	0.01	241	2	0.01	1	472	>10000	1.25	12	<1	9	<5	<0.01	<10	<10	1	<10	758	3
139451	1.9	1.67	58	30	<0.5	5	0.22	<1	66	39	58	12.55	<1	0.35	<10	0.37	632	275	0.01	29	1541	109	>5.00	<5	2	4	<5	0.05	<10	15	31	<10	166	7
139452	1.5	1.22	73	96	<0.5	<5	0.19	1	19	15	23	8.95	<1	0.39	<10	0.26	388	170	0.01	6	1528	78	2.30	<5	1	4	<5	0.02	<10	<10	26	<10	71	5
139453	2.0	1.24	115	40	<0.5	7	0.15	1	41	27	43	14.05	<1	0.36	<10	0.22	426	205	0.01	16	1375	43	5.00	<5	1	3	<5	0.03	<10	15	27	<10	101	7
139454	1.9	1.65	157	36	<0.5	7	0.19	2	61	16	78	14.36	<1	0.37	<10	0.32	600	199	0.01	22	1421	47	>5.00	<5	1	4	<5	0.03	<10	17	30	<10	173	8
139455	1.9	1.54	69	54	<0.5	<5	0.25	<1	61	17	36	10.80	<1	0.47	<10	0.28	475	321	0.01	25	1741	68	>5.00	<5	1	7	<5	0.03	<10	12	29	<10	144	6
139456	2.1	2.18	158	38	<0.5	6	0.29	2	74	26	42	13.89	<1	0.44	<10	0.42	718	609	0.01	26	1782	71	>5.00	<5	2	5	<5	0.03	<10	16	45	<10	221	8
139457	1.8	1.49	200	69	<0.5	<5	0.28	3	38	23	15	9.37	<1	0.43	<10	0.28	461	389	0.01	12	1768	55	>5.00	<5	1	5	<5	0.02	<10	<10	30	<10	160	5
139458	1.3	1.38	41	151	<0.5	<5	0.27	<1	22	18	11	7.07	<1	0.54	<10	0.23	370	92	0.02	6	1776	24	3.10	<5	2	6	<5	0.03	<10	<10	31	<10	87	4
139459	1.3	1.95	32	136	<0.5	<5	0.69	<1	19	23	59	5.18	<1	0.34	<10	0.76	1457	3	0.02	2	1689	18	0.36	<5	2	15	<5	0.08	<10	<10	49	<10	114	3
139460	1.6	1.76	31	177	<0.5	<5	0.47	<1	16	12	36	4.77	<1	0.49	<10	0.56	999	2	0.02	1	1805	20	0.54	<5	2	8	<5	0.10	<10	<10	39	<10	64	3
139461	2.1	1.61	53	156	<0.5	<5	0.49	1	18	11	42	4.88	<1	0.38	<10	0.58	978	13	0.01	2	1882	25	0.50	<5	2	8	<5	0.10	<10	<10	36	<10	95	3
139462	2.5	1.83	107	185	<0.5	<5	0.68	1	32	7	71	4.99	<1	0.47	<10	0.65	1506	13	0.01	6	1918	31	0.66	5	2	12	<5	0.11	<10	<10	44	<10	108	3
139463	3.1	1.78	105	152	<0.5	<5	0.44	1	27	7	57	5.70	<1	0.36	<10	0.73	1221	17	0.01	6	1800	33	0.51	5	2	7	<5	0.11	<10	<10	41	<10	77	3
139464	2.1	1.46	97	146	<0.5	<5	0.63	1	17	8	36	4.40	<1	0.39	<10	0.53	1140	4	0.01	2	1729	22	0.44	<5	2	12	<5	0.07	<10	<10	35	<10	65	3
139465	2.3	1.74	61	139	<0.5	<5	0.59	1	18	12	48	5.34	<1	0.33	<10	0.68	1663	<2	0.01	1	1532	23	0.91	<5	2	11	<5	0.08	<10	<10	42	<10	99	3
139466	2.7	1.39	186	42	<0.5	11	0.21	1	46	22	46	13.27	<1	0.42	<10	0.22	451	86	0.01	13	1624	67	>5.00	<5	1	5	<5	0.05	<10	14	28	<10	121	8
139467	1.1	1.65	271	38	<0.5	5	0.23	3	50	15	68	11.78	<1	0.33	<10	0.30	662	67	0.01	16	1456	47	>5.00	<5	1	4	<5	0.04	<10	13	26	<10	73	6
139468	1.4	1.10	64	252	<0.5	<5	0.17	<1	8	10	7	6.55	<1	0.47	<10	0.15	274	79	0.03	<1	1493	36	0.70	<5	1	9	<5	0.12	<10	<10	34	<10	23	4
139469	0.6	1.10	40	201	<0.5	<5	0.39	<1	10	13	19	3.76	<1	0.44	<10	0.19	438	5	0.02	<1	1815	17	0.63	<5	1	8	<5	0.10	<10	<10	28	<10	35	3
120046	0.2	0.64	27	101	<0.5	<5	2.34	<1	10	47	<1	3.33	<1	0.32	<10	0.93	1171	10	0.02	1	913	9	0.50	<5	4	125	<5	<0.01	<10	<10	20	<10	46	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3008RJ

Date : Sep-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 19

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120047	0.4	1.09	75	71	<0.5	<5	2.61	1	10	65	14	3.84	<1	0.32	<10	0.88	1165	4	0.01	2	894	11	0.96	<5	2	97	<5	<0.01	<10	<10	30	<10	67	2
120048	0.4	1.38	20	79	<0.5	<5	3.07	<1	11	43	31	3.88	<1	0.23	<10	0.87	1177	4	0.02	1	917	9	0.56	<5	3	84	<5	<0.01	<10	<10	47	<10	73	2
120049	0.7	1.23	29	75	<0.5	<5	3.10	<1	10	56	51	3.55	<1	0.20	<10	0.84	1218	5	0.02	2	882	10	0.52	<5	4	89	<5	<0.01	<10	<10	48	<10	81	2
120050	<0.2	0.93	<5	229	<0.5	<5	0.44	<1	9	104	<1	2.03	<1	0.48	<10	0.60	555	<2	0.06	5	767	6	<0.01	<5	2	43	5	0.12	<10	<10	38	<10	50	2
120051	0.7	0.77	81	100	<0.5	<5	3.57	1	10	53	26	3.23	<1	0.36	<10	0.78	1420	2	0.02	2	876	27	0.63	<5	4	152	<5	<0.01	<10	<10	21	<10	59	2
120052	0.5	0.69	48	196	<0.5	<5	3.01	1	11	68	8	3.44	<1	0.30	<10	0.79	1105	3	0.01	2	908	62	0.80	<5	3	136	<5	<0.01	<10	<10	23	<10	123	2
120053	0.4	0.65	30	264	<0.5	<5	3.51	2	11	34	59	3.91	1	0.37	10	0.76	1298	3	0.02	5	993	6	0.49	<5	3	154	8	<0.01	<10	<10	30	<10	73	3
120054	3.4	0.50	67	243	<0.5	<5	2.48	18	14	46	223	4.49	<1	0.35	<10	0.83	1155	11	0.02	5	972	1553	0.95	<5	3	158	5	<0.01	<10	<10	25	<10	2160	3
120055	0.8	0.47	161	144	<0.5	<5	2.74	2	8	45	31	3.33	<1	0.33	<10	0.48	1051	3	0.01	3	777	259	1.62	<5	2	142	6	<0.01	<10	<10	17	<10	188	3
120056	0.3	0.84	45	153	<0.5	<5	2.94	2	11	50	27	3.62	<1	0.31	<10	0.63	1305	2	0.01	4	833	20	0.70	<5	2	106	5	<0.01	<10	<10	34	<10	80	3
120057	0.9	0.98	287	76	<0.5	<5	2.27	2	9	41	17	4.65	<1	0.31	<10	0.55	1253	4	0.01	4	739	15	2.39	5	2	93	5	<0.01	<10	<10	31	<10	48	4
120058	0.5	1.11	63	288	<0.5	<5	3.13	2	14	42	43	4.07	<1	0.29	<10	0.74	1195	9	0.01	6	879	10	0.92	<5	3	159	6	<0.01	<10	<10	39	<10	87	3
120059	0.4	0.88	48	192	<0.5	<5	2.80	8	10	30	34	3.44	<1	0.34	10	0.66	1064	2	0.02	4	924	104	0.62	<5	3	119	7	<0.01	<10	<10	31	<10	914	3
120060	<0.2	1.23	196	190	<0.5	<5	3.02	2	10	44	24	3.61	<1	0.36	10	0.74	1030	4	0.02	4	885	8	0.62	<5	3	148	7	<0.01	<10	<10	42	<10	68	3
120061	<0.2	1.12	34	145	<0.5	<5	3.04	1	10	26	15	3.70	<1	0.38	11	0.84	1123	3	0.02	4	949	4	0.52	<5	4	166	7	<0.01	<10	<10	35	<10	52	3
120062	0.9	1.23	39	107	<0.5	<5	2.94	2	10	38	26	3.66	<1	0.34	10	0.87	1071	12	0.02	3	913	25	0.49	<5	4	141	7	<0.01	<10	<10	38	<10	89	3
120063	0.2	0.77	46	115	<0.5	<5	2.17	1	9	35	13	3.36	<1	0.40	<10	0.71	1034	8	0.01	4	854	7	0.54	<5	3	106	7	<0.01	<10	<10	22	<10	46	3
120064	0.6	0.71	40	151	<0.5	<5	2.66	1	9	39	20	3.40	<1	0.31	<10	0.71	1091	11	0.02	3	883	4	0.51	<5	3	159	7	<0.01	<10	<10	25	<10	45	3
120065	0.2	0.51	30	102	<0.5	<5	3.07	1	7	42	15	3.15	1	0.33	<10	0.67	1028	8	0.02	2	760	15	0.43	<5	3	232	6	<0.01	<10	<10	17	<10	57	3
120066	0.6	0.63	422	80	<0.5	<5	4.37	1	8	45	11	3.25	<1	0.30	<10	0.50	1511	4	0.01	3	687	15	1.19	6	3	110	5	<0.01	<10	<10	21	<10	59	3
120067	1.2	0.58	170	66	<0.5	<5	2.03	2	10	36	87	3.87	<1	0.35	<10	0.54	1157	13	0.01	3	814	30	1.36	6	2	89	5	<0.01	<10	<10	21	<10	102	3
120068	2.4	0.65	126	70	0.5	<5	3.78	2	16	23	366	4.44	<1	0.42	<10	0.67	1694	9	0.01	4	1066	18	1.06	6	3	124	<5	<0.01	<10	<10	31	<10	145	3
120069	4.9	0.49	56	84	<0.5	<5	3.48	3	15	21	230	4.67	1	0.43	<10	0.80	1677	8	0.01	4	1109	38	0.90	36	5	273	5	<0.01	<10	<10	22	<10	147	3
120070	1.5	1.28	40	190	<0.5	<5	2.89	2	18	17	227	4.80	<1	0.46	<10	0.98	1645	6	0.01	5	1286	6	0.45	<5	5	135	6	<0.01	<10	<10	53	<10	199	3
120071	2.4	0.65	212	171	0.5	<5	4.04	2	15	14	214	4.60	<1	0.42	<10	0.79	1725	11	0.01	4	1115	51	1.64	7	3	154	5	<0.01	<10	<10	27	<10	198	3
120072	4.0	0.56	1925	379	0.7	<5	2.48	2	17	12	260	4.45	<1	0.44	<10	0.83	2104	7	0.01	4	1226	21	0.73	18	3	138	<5	<0.01	<10	<10	23	<10	187	3
120073	1.1	0.59	225	72	0.6	<5	1.80	3	19	15	221	4.92	<1	0.44	<10	0.84	2388	15	0.01	5	1209	17	0.58	<5	4	116	<5	<0.01	<10	<10	31	<10	197	3
120074	6.3	0.50	55	87	0.6	<5	4.04	4	17	39	164	5.06	1	0.39	<10	1.17	3277	9	0.01	6	1149	54	0.54	18	4	329	<5	<0.01	<10	<10	22	<10	234	3
120075	193.1	0.97	207	255	<0.5	103	6.27	6	19	29	3771	4.06	3	0.18	<10	0.22	744	65	0.03	38	658	400	1.54	221	2	210	<5	0.07	<10	<10	27	<10	274	10
120076	1.0	0.73	31	139	0.6	<5	3.23	1	22	21	93	5.50	<1	0.51	<10	1.02	2474	4	0.02	4	1209	52	0.36	<5	5	158	<5	<0.01	<10	<10	31	<10	234	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3008RJ

Date : Sep-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 19

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120077	7.6	1.29	47	160	<0.5	<5	3.75	1	19	28	139	5.17	<1	0.42	10	0.88	1832	13	0.02	3	1138	27	0.49	<5	4	153	<5	<0.01	<10	<10	49	<10	182	2
120078	2.8	1.81	296	132	<0.5	<5	13.22	8	13	7	117	4.78	<1	0.31	<10	1.49	3318	32	0.01	<1	862	28	0.26	<5	4	560	<5	<0.01	<10	<10	35	<10	365	2
120079	3.7	1.22	60	172	<0.5	<5	6.91	6	14	14	181	4.23	<1	0.44	<10	0.80	2151	29	0.01	<1	1085	197	1.06	<5	3	293	<5	<0.01	<10	<10	32	<10	502	2
120080	0.7	0.61	26	159	0.6	<5	3.66	1	11	10	31	3.89	<1	0.44	10	0.80	1803	2	0.02	<1	1064	100	0.88	<5	3	205	<5	<0.01	<10	<10	19	<10	140	2
120081	0.9	0.54	142	158	0.5	<5	1.73	3	12	26	17	4.02	<1	0.42	<10	0.19	597	2	0.01	1	1056	38	4.49	<5	2	93	<5	<0.01	<10	<10	12	<10	148	3
120082	1.7	0.45	133	150	<0.5	<5	6.99	3	9	25	16	3.55	<1	0.34	<10	0.13	1413	2	0.01	<1	760	39	4.33	<5	2	258	<5	<0.01	<10	<10	9	<10	104	2
120083	1.6	0.56	156	171	<0.5	<5	6.82	3	10	32	31	3.58	<1	0.39	<10	0.27	1437	<2	0.01	1	975	26	3.39	<5	3	257	<5	<0.01	<10	<10	13	<10	98	3
120084	14.4	0.56	113	162	0.5	<5	4.14	4	10	23	58	3.60	<1	0.38	<10	0.30	1176	<2	0.01	1	997	682	3.02	<5	2	163	<5	<0.01	<10	<10	14	<10	312	3
120085	3.9	1.56	22	202	<0.5	<5	3.84	2	12	31	53	4.07	<1	0.42	13	1.05	1468	3	0.03	1	1009	153	0.88	<5	4	185	<5	<0.01	<10	<10	41	<10	354	2
120086	<0.2	1.49	17	202	<0.5	<5	3.97	<1	11	25	25	4.16	<1	0.38	12	1.05	1464	<2	0.03	<1	1056	18	0.60	<5	4	176	<5	<0.01	<10	<10	42	<10	126	3
120087	0.2	1.32	26	217	<0.5	<5	4.43	<1	11	21	27	3.94	<1	0.40	14	0.88	1625	2	0.03	<1	1068	16	0.66	<5	3	205	<5	<0.01	<10	<10	34	<10	128	2
120088	0.2	1.18	46	212	<0.5	<5	4.26	1	11	17	31	4.19	<1	0.38	10	0.84	1483	4	0.03	<1	1024	17	1.08	<5	3	178	<5	<0.01	<10	<10	30	<10	132	2
120089	0.4	1.31	12	250	<0.5	<5	3.43	<1	11	19	25	4.27	<1	0.37	10	1.00	1637	3	0.03	1	1009	25	0.49	<5	3	163	<5	<0.01	<10	<10	30	<10	131	2
120090	1.3	1.76	10	200	<0.5	<5	4.10	<1	13	13	105	4.77	<1	0.35	10	1.09	1843	2	0.03	1	1088	37	0.53	<5	4	176	<5	<0.01	<10	<10	50	<10	129	2
120091	1.8	1.71	7	181	<0.5	<5	4.30	<1	14	12	123	4.71	<1	0.32	11	1.01	1920	6	0.03	1	1059	22	0.38	<5	4	177	<5	<0.01	<10	<10	48	<10	154	2
120092	0.3	0.76	6	1076	0.5	<5	3.35	<1	12	9	47	4.59	<1	0.41	14	1.13	1938	2	0.04	<1	1101	20	0.36	<5	4	203	<5	<0.01	<10	<10	34	<10	123	2
120093	0.7	1.85	9	382	<0.5	<5	3.72	<1	14	13	61	4.85	<1	0.38	13	1.10	2068	<2	0.03	1	1177	18	0.59	<5	4	171	<5	<0.01	<10	<10	52	<10	130	2
120094	0.4	2.12	<5	303	<0.5	<5	4.45	<1	19	7	75	5.09	<1	0.40	11	1.13	2281	2	0.03	1	1271	16	0.39	<5	4	246	<5	0.01	<10	<10	63	<10	115	2
120095	0.3	2.04	6	206	<0.5	<5	4.67	<1	13	10	50	4.75	<1	0.33	12	1.18	2146	3	0.03	<1	1192	18	0.36	<5	4	234	<5	<0.01	<10	<10	53	<10	118	2
120096	0.9	2.28	17	260	<0.5	<5	4.67	<1	19	8	78	5.23	<1	0.42	13	1.16	2201	2	0.03	1	1238	20	0.62	<5	4	211	<5	0.01	<10	<10	62	<10	131	2
120097	0.7	1.21	24	209	<0.5	<5	3.80	1	11	11	22	3.57	<1	0.31	13	0.80	1594	4	0.03	1	1033	15	0.75	<5	2	187	8	<0.01	<10	<10	36	<10	79	4
120098	0.4	1.77	18	209	<0.5	<5	3.84	2	12	8	39	4.01	<1	0.35	15	0.93	1703	2	0.03	2	1170	17	0.85	<5	3	223	8	0.01	<10	<10	44	<10	87	4
120099	0.7	1.72	29	173	<0.5	<5	3.42	2	12	10	26	4.08	<1	0.33	12	0.90	1597	2	0.03	2	1174	15	1.11	<5	2	173	6	<0.01	<10	<10	42	<10	93	4
120100	<0.2	1.02	<5	235	0.7	<5	0.51	1	8	76	<1	1.95	<1	0.50	<10	0.61	553	<2	0.06	5	740	<2	0.01	<5	2	59	8	0.14	<10	<10	41	<10	45	3
120101	0.6	1.98	24	208	<0.5	<5	3.64	2	13	8	37	4.18	<1	0.39	13	0.98	2026	<2	0.03	3	1074	14	0.59	<5	2	193	5	<0.01	<10	<10	37	<10	105	4
120102	0.9	1.09	351	150	<0.5	<5	4.89	2	12	26	18	4.00	<1	0.30	11	0.51	1658	3	0.02	3	1041	25	2.45	5	2	255	8	<0.01	<10	<10	28	<10	75	3
120103	0.7	0.93	384	139	<0.5	<5	4.24	2	12	15	15	3.82	<1	0.33	10	0.38	1270	16	0.03	3	1038	20	2.84	<5	1	249	7	<0.01	<10	<10	23	<10	70	3
120104	0.4	1.32	113	148	<0.5	<5	3.31	1	11	14	22	3.60	<1	0.26	10	0.70	1434	2	0.03	3	1024	5	1.37	<5	2	162	5	<0.01	<10	<10	35	<10	71	3
120105	1.0	1.76	34	184	<0.5	<5	3.34	2	13	12	41	4.11	<1	0.38	13	0.92	1769	5	0.03	3	1149	6	0.86	<5	3	183	5	<0.01	<10	<10	42	<10	80	4
120106	7.6	0.58	236	106	<0.5	<5	3.56	3	11	27	64	3.65	<1	0.26	<10	0.41	1214	36	0.02	3	820	96	2.32	7	1	153	6	<0.01	<10	<10	18	<10	324	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 19

Sample type:

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3008RJ

Date : Sep-04-08

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120107	2.9	0.93	714	123	<0.5	<5	2.68	2	13	16	56	4.14	<1	0.39	10	0.58	1112	16	0.03	3	1140	21	3.08	9	2	155	6	<0.01	<10	<10	22	<10	109	4
120108	1.4	1.76	57	139	<0.5	<5	1.60	2	13	19	42	4.19	<1	0.34	13	1.05	1254	5	0.02	3	1141	13	0.99	<5	2	79	6	<0.01	<10	<10	39	<10	91	3
120109	1.3	1.56	52	181	<0.5	<5	2.03	2	12	16	35	3.48	<1	0.43	12	0.71	1070	<2	0.03	3	1077	16	0.86	<5	2	98	7	<0.01	<10	<10	34	<10	82	3
120110	2.1	0.56	149	111	<0.5	<5	7.68	3	11	23	53	4.26	<1	0.29	<10	0.36	2243	3	0.02	3	739	40	2.56	6	2	248	7	<0.01	<10	<10	17	<10	114	3
120111	6.9	0.45	193	135	<0.5	<5	5.08	2	9	17	34	3.16	<1	0.33	<10	0.35	1438	3	0.02	2	825	32	2.06	7	1	230	7	<0.01	<10	<10	13	<10	102	3
120112	1.6	0.49	152	243	0.5	<5	3.77	2	12	17	21	3.60	<1	0.36	10	0.52	1442	2	0.02	3	1107	14	0.86	<5	2	176	6	<0.01	<10	<10	18	<10	68	3
120113	2.4	0.99	78	199	0.5	<5	3.39	2	12	16	26	3.75	<1	0.43	10	0.61	1575	<2	0.02	3	1068	28	0.98	<5	2	155	6	<0.01	<10	<10	24	<10	122	3
120114	4.6	0.95	101	142	<0.5	<5	2.53	2	10	24	32	3.56	1	0.33	<10	0.57	1324	3	0.02	3	1010	56	1.40	<5	2	124	6	<0.01	<10	<10	24	<10	214	3
120115	0.3	1.97	11	93	1.1	<5	1.24	3	17	23	51	4.68	<1	0.13	10	1.11	1127	<2	0.05	3	1343	14	0.15	<5	6	58	<5	0.21	<10	<10	102	<10	341	9
120116	0.9	2.10	42	64	0.6	<5	2.31	3	17	28	80	5.25	1	0.10	<10	1.41	1450	2	0.03	2	1135	60	0.45	<5	7	122	6	0.10	<10	<10	117	<10	333	5
120117	0.3	2.09	10	190	1.1	<5	2.10	2	21	18	57	4.86	<1	0.13	<10	1.46	973	3	0.03	3	1279	4	0.25	<5	7	131	<5	0.20	<10	<10	120	<10	168	5

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3008-SG1

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 19**
Attn: **Sue Deane**

Sep-04-08

We *hereby certify* the following geochemical analysis of 22 soil samples submitted Aug-21-08

Sample Name	Au ppb
6222464	4
6222812	1
6222920	4
6222937	2
6222948	<1
6223236	1
6223472	2
6223642	<1
6223961	1
6223992	<1
6224148	8
6224271	4
6224401	3
6224655	4
6225027	2
6225144	4
6225288	7
6225314	2
6225605	<1
6225726	24
6225813	5
6225841	27
*0218	887
*BLANK	<1

Certified by _____

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3008-SG2

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 19**
Attn: **Sue Deane**

Sep-04-08

We *hereby certify* the following geochemical analysis of 14 soil samples submitted Aug-21-08

Sample Name	Au ppb
6226209	6
6226681	6
6226807	1
6227042	12
6227414	7
6227429	4
6227490	6
6227726	4
6227800	1
6228233	5
6228521	16
6228669	7
6228796	10
6229278	31
*0218	912
*BLANK	<1

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3008SJ**

Date : Sep-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 19

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
6222464	<0.2	1.84	17	64	0.6	<5	0.23	2	20	67	47	4.23	1	0.05	11	1.10	465	<2	0.01	104	1099	15	0.02	<5	6	34	<5	0.01	<10	<10	44	<10	120	4
6222812	<0.2	1.77	18	61	0.6	<5	0.27	2	25	66	64	4.51	<1	0.04	<10	1.03	610	<2	0.01	128	1252	14	0.03	<5	6	57	<5	<0.01	<10	<10	39	<10	127	5
6222920	0.2	2.00	18	81	0.8	<5	0.29	2	36	72	67	5.08	<1	0.04	<10	1.09	922	<2	0.01	151	1281	20	0.03	<5	7	62	<5	<0.01	<10	<10	43	<10	153	4
6222937	0.2	2.02	15	84	0.7	<5	0.29	2	31	78	66	4.87	<1	0.05	<10	1.12	739	<2	0.01	146	1298	17	0.04	<5	8	68	<5	<0.01	<10	<10	45	<10	150	5
6222948	<0.2	1.98	14	73	0.7	<5	0.28	2	28	73	65	4.85	<1	0.04	<10	1.13	836	<2	0.01	138	1234	14	0.04	<5	7	60	<5	<0.01	<10	<10	43	<10	142	5
6223236	<0.2	1.87	9	49	0.5	<5	0.28	2	18	71	42	4.14	<1	0.04	<10	1.10	413	<2	0.01	111	1260	10	0.06	<5	5	63	<5	<0.01	<10	<10	40	<10	113	3
6223472	<0.2	1.96	9	58	0.6	<5	0.25	2	22	75	50	4.31	<1	0.04	<10	1.14	601	<2	0.01	122	1095	10	0.05	<5	6	61	<5	<0.01	<10	<10	41	<10	125	5
6223642	<0.2	1.90	16	76	0.7	<5	0.43	2	28	68	61	4.83	<1	0.04	<10	1.18	870	<2	0.01	125	1265	15	0.28	<5	6	99	<5	0.01	<10	<10	45	<10	138	4
6223961	<0.2	1.92	10	59	0.6	<5	0.26	2	22	74	47	4.32	<1	0.04	<10	1.11	543	<2	0.01	120	1154	10	0.03	<5	6	58	<5	<0.01	<10	<10	42	<10	123	4
6223992	<0.2	1.87	9	51	0.5	<5	0.22	2	21	71	42	4.20	<1	0.03	<10	1.08	497	<2	0.01	111	1016	9	0.01	<5	5	41	<5	0.01	<10	<10	40	<10	112	5
6224148	<0.2	2.04	11	58	0.6	<5	0.21	2	23	75	47	4.56	<1	0.04	<10	1.13	560	<2	0.01	118	1096	11	0.01	<5	6	39	<5	0.01	<10	<10	43	<10	119	4
6224271	<0.2	1.77	10	61	0.6	<5	0.22	1	23	68	45	4.06	<1	0.04	<10	1.03	550	<2	0.01	112	1014	10	0.03	<5	5	40	<5	0.01	<10	<10	40	<10	113	5
6224401	<0.2	2.08	13	83	0.7	<5	0.24	2	29	77	59	5.02	<1	0.05	<10	1.17	749	<2	0.01	140	1208	12	0.03	<5	7	44	<5	0.01	<10	<10	47	<10	144	5
6224655	<0.2	2.03	14	78	0.7	<5	0.18	2	35	72	66	5.24	1	0.04	<10	1.06	930	<2	0.01	154	1190	12	0.02	<5	7	38	<5	<0.01	<10	<10	44	<10	146	6
6225027	<0.2	2.34	15	89	0.7	<5	0.19	2	39	84	68	5.28	<1	0.04	<10	1.21	1197	<2	0.01	152	1151	17	0.03	<5	6	36	<5	0.01	<10	<10	47	<10	161	6
6225144	<0.2	2.52	15	75	0.9	<5	0.20	2	39	72	54	4.89	<1	0.04	<10	1.03	1173	<2	0.01	117	1335	19	0.04	<5	5	34	<5	0.02	<10	<10	44	<10	139	9
6225288	<0.2	2.23	18	73	0.8	<5	0.18	2	44	75	68	5.40	<1	0.04	<10	1.10	1222	<2	0.01	141	1196	17	0.02	<5	6	30	<5	0.02	<10	<10	46	<10	152	6
6225314	<0.2	2.08	12	61	0.6	<5	0.16	2	30	71	52	4.77	<1	0.03	<10	1.11	808	<2	0.01	121	938	12	0.01	<5	5	25	<5	0.02	<10	<10	45	<10	133	4
6225605	<0.2	2.18	17	104	0.8	<5	0.23	2	39	75	68	5.41	<1	0.04	<10	1.16	1118	<2	0.01	150	1188	15	0.04	<5	7	46	<5	0.01	<10	<10	47	<10	166	5
6225726	<0.2	2.07	20	95	0.8	<5	0.21	2	34	67	57	4.99	<1	0.04	<10	1.08	1025	<2	0.01	127	1219	15	0.03	<5	5	39	<5	0.02	<10	<10	48	<10	153	6
6225813	<0.2	2.22	21	96	0.9	<5	0.17	2	44	62	68	5.68	<1	0.04	<10	1.03	2327	<2	0.01	145	1334	15	0.04	<5	5	38	<5	0.02	<10	<10	50	<10	219	7
6225841	<0.2	2.34	17	85	1.0	<5	0.24	2	28	64	41	4.92	<1	0.04	11	1.00	1173	2	0.01	116	1329	15	0.04	<5	4	45	<5	0.02	<10	<10	47	<10	166	8
6226209	0.2	2.26	23	83	0.9	<5	0.21	2	41	73	71	5.88	<1	0.04	<10	1.11	1354	<2	0.01	157	1364	18	0.04	6	5	42	<5	0.01	<10	<10	54	<10	177	7
6226681	0.2	1.93	9	77	0.8	<5	0.28	1	18	30	26	4.09	<1	0.03	10	0.80	801	<2	0.01	54	1003	9	0.02	<5	3	36	<5	0.08	<10	<10	51	<10	107	4
6226807	<0.2	1.92	9	65	0.7	<5	0.28	2	15	46	20	4.22	<1	0.03	10	0.87	587	<2	0.01	64	1125	13	0.03	<5	3	40	<5	0.05	<10	<10	47	<10	110	6
6227042	0.3	2.14	30	102	0.9	<5	0.21	3	53	67	79	5.93	<1	0.04	<10	1.03	1858	<2	0.01	167	1456	21	0.06	5	5	41	<5	0.01	<10	<10	50	<10	201	6
6227414	0.2	1.95	23	108	0.8	<5	0.20	2	50	60	84	5.57	<1	0.05	<10	0.95	3202	<2	0.01	153	1362	15	0.12	5	4	38	<5	0.01	<10	<10	45	<10	248	6
6227429	<0.2	2.12	33	241	1.2	<5	0.37	4	80	46	131	8.05	1	0.03	<10	0.80	9205	2	0.01	245	1931	14	0.15	5	5	83	<5	0.01	<10	<10	54	<10	463	8
6227490	<0.2	2.01	35	108	0.9	<5	0.22	3	47	56	76	6.06	<1	0.04	<10	0.97	2806	<2	0.01	141	1229	12	0.09	<5	3	44	<5	0.01	<10	<10	51	<10	284	6
6227726	<0.2	2.10	19	116	1.1	<5	0.24	3	46	53	82	5.01	<1	0.05	10	0.98	2368	<2	0.01	173	1264	12	0.05	<5	5	37	<5	0.03	<10	<10	47	<10	272	7

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3008SJ

Date : Sep-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 19

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
6227800	<0.2	1.94	20	99	0.7	<5	0.22	2	37	50	60	5.44	<1	0.04	<10	0.97	2343	<2	0.01	119	1161	12	0.13	<5	3	38	<5	0.02	<10	<10	49	<10	223	7
6228233	0.3	2.03	25	81	0.8	<5	0.17	3	43	55	84	6.10	<1	0.04	11	1.04	1526	<2	0.01	117	1357	13	0.05	6	3	33	<5	0.02	<10	<10	49	<10	206	8
6228521	0.3	2.98	38	131	1.3	<5	0.48	4	76	79	139	9.90	<1	0.07	14	1.21	2662	<2	0.01	216	1978	21	0.13	6	5	86	<5	0.01	<10	<10	74	<10	398	9
6228669	<0.2	2.18	21	91	0.9	<5	0.15	3	58	62	115	6.59	<1	0.05	11	1.16	2619	<2	0.01	170	1588	10	0.07	<5	4	27	<5	0.01	<10	<10	51	<10	266	7
6228796	<0.2	2.00	20	89	0.7	<5	0.18	2	41	61	85	5.99	<1	0.05	11	1.11	1922	<2	0.01	141	1249	11	0.05	5	4	33	<5	0.02	<10	<10	51	<10	213	5
6229278	0.5	2.69	37	132	1.2	<5	0.26	4	76	82	131	7.81	<1	0.05	10	1.25	3224	<2	0.02	237	1841	25	0.06	6	7	47	<5	0.02	<10	<10	64	<10	300	7

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 35 Years

Assay Certificate

8V-3063-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 20**
Attn: **Sue Deane**

Sep-19-08

We hereby certify the following assay of 22 core samples submitted Aug-27-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120118	0.08	0.11	1.1
120119	0.40		1.1
120120	0.24		2.3
120121	0.64		11.7
120122	0.14		2.1
120123	0.13		0.5
120124	0.31		0.7
120125	1.76		160
120126	0.19		1.5
120127	0.39	0.32	0.9
120128	0.22		1.1
120129	1.57		7.9
120130	0.24		1.4
120131	0.04		0.2
120132	0.09		1.0
120133	0.08		0.4
120134	0.24		5.4
120135	0.06		1.9
120136	0.10		1.4
120137	0.07	0.07	0.4
120138	0.02		<0.1
120139	0.02		<0.1
*0218	0.88		
*BLANK	<0.01		

Certified by _____

*Quality Assaying for over 35 Years***Assay Certificate****8V-3063-RA2**Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 20**
Attn: **Sue Deane**

Sep-19-08

We hereby certify the following assay of 22 core samples
submitted Aug-27-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120140	0.05	0.06	0.3
120141	0.08		0.4
120142	0.03		<0.1
120143	0.09		<0.1
120144	0.18		0.9
120145	0.07		0.2
120146	0.04		0.2
120147	0.20		0.7
120148	0.08		<0.1
120149	0.11	0.14	<0.1
120150	<0.01		<0.1
120151	0.76		1.4
120152	0.12		0.6
120153	0.05		<0.1
120154	2.15		1.8
120155	0.09		<0.1
120156	0.05		<0.1
120157	0.03		<0.1
120158	0.17		<0.1
120159	0.11	0.10	0.3
120160	0.34		0.2
120161	0.09		<0.1
*0218	0.92		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 35 Years

Assay Certificate

8V-3063-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 20**
Attn: **Sue Deane**

Sep-19-08

We hereby certify the following assay of 22 core samples submitted Aug-27-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120162	0.10	0.10	<0.1
120163	0.14		0.2
120164	0.16		1.2
120165	6.55		3.9
120166	0.30		6.4
120167	0.19		1.0
120168	1.71		8.2
120169	0.33		2.2
120170	0.17		2.5
120171	0.15	0.16	3.3
120172	0.21		2.6
120173	0.30		4.1
120174	0.22		3.2
120175	6.25		2.9
120176	0.28		3.6
120177	0.32		3.5
120178	0.27		1.8
120179	0.44		1.7
120180	0.05		1.4
120181	0.01	0.01	0.5
120182	<0.01		0.1
120183	0.01		<0.1
*0218	0.92		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 35 Years

Assay Certificate

8V-3063-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 20**
Attn: **Sue Deane**

Sep-19-08

We hereby certify the following assay of 22 core samples submitted Aug-27-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120184	<0.01	<0.01	<0.1
120185	0.05		0.2
120186	0.02		5.7
120187	0.07		11.6
120188	0.01		2.9
120189	0.03		0.7
120190	0.07		1.4
120191	0.03		1.4
120192	0.46		10.5
120193	0.08	0.06	3.3
120194	0.05		23.5
120195	0.03		1.9
120196	0.03		2.1
120197	0.24		2.1
120198	0.02		23.2
120199	0.02		1.0
120200	0.01		<0.1
120201	0.05		2.5
120202	0.21		9.6
120203	0.36	0.41	17.8
120204	0.15		24.3
120205	0.02		2.5
*0218	0.91		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 35 Years

Assay Certificate

8V-3063-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 20**
Attn: **Sue Deane**

Sep-19-08

We hereby certify the following assay of 22 core samples submitted Aug-27-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120206	0.11	0.09	3.7
120207	0.03		0.5
120208	0.01		2.9
120209	0.29		1.1
120210	0.30		1.3
120211	0.20		1.2
120212	0.11		1.7
120213	0.18		3.0
120214	0.31		2.3
120215	0.11	0.10	1.0
120216	0.18		1.6
120217	0.07		0.3
120218	0.11		<0.1
120219	0.02		<0.1
120220	0.11		1.6
120221	0.10		2.1
120222	0.08		0.8
120223	0.15		1.1
120224	0.06		1.7
120225	0.02	<0.01	<0.1
120226	0.07		0.2
120227	0.11		1.8
*0218	0.92		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 35 Years

Assay Certificate

8V-3063-RA6

Company: **Ascot Resources Ltd**
 Project: **Dilworth/shipment 20**
 Attn: **Sue Deane**

Sep-19-08

We hereby certify the following assay of 22 pulp samples submitted Aug-27-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %	Zn %
120228	0.06	0.07	1.4		
120229	0.07		1.9		
120230	0.51		7.1		
120231	0.21		1.1		
120232	0.16		2.1		
120360	0.31		0.6		
120361	0.50		0.3		
120362	0.46		13.0		
120363	1.02		1.6		
120364	0.43	0.45	0.6		
139434	0.13		7.9		
139435	1.99		7.2		
139436	1.47		15.9		
139437	0.41		9.2		1.22
139438	0.39		2.3		
139439	0.08		0.8		
139440	0.49		19.7	1.23	
139441	1.67		136	3.38	
139442	1.42		34.0		2.09
139443	1.06	1.01	69.3	1.35	2.44
139444	2.31		39.4		1.17
139445	0.12		6.1		
*0218	0.88				
*CCu-1c				0.35	3.93
*BLANK	<0.01			<0.01	<0.01

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 35 Years

Assay Certificate

8V-3063-RA7

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 20**
Attn: **Sue Deane**

Sep-19-08

We hereby certify the following assay of 22 core samples submitted Aug-27-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
139446	0.11	0.11	3.1
139447	0.23		4.2
139448	0.21		5.0
139449	0.23		4.9
139450	0.01		0.3
139470	0.03		0.7
139471	0.04		0.5
139472	0.07		0.7
139473	0.03		0.6
139474	<0.01	0.01	0.5
139475	<0.01		0.3
139476	0.01		0.5
PB08#7	<0.01		0.3
PB08#8	<0.01		<0.1
PB08#9	0.03		<0.1
PB08#10	<0.01		<0.1
PB08#11	0.02		<0.1
PB08#12	0.01		<0.1
PB08#13	0.01		<0.1
PB08#14	0.02	0.01	0.1
PB08#15	0.04		0.2
PB08#16	0.01		<0.1
*0218	0.88		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 35 Years

Assay Certificate

8V-3063-RA8

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 20**
Attn: **Sue Deane**

Sep-19-08

We hereby certify the following assay of 22 pulp samples submitted Aug-27-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
PB08#17	<0.01	0.01	<0.1
PB08#18	<0.01		<0.1
PB08#19	<0.01		5.2
PB08#20	0.02		<0.1
PB08#21	<0.01		<0.1
PB08#22	<0.01		<0.1
PB08#23	<0.01		<0.1
PB08#24	0.02		0.6
PB08#25	<0.01		<0.1
49475	0.15	0.15	6.2
49476	0.09		4.3
49477	0.13		2.0
49478	0.09		5.1
49479	0.04		2.3
49480	0.05		1.7
49481	0.22		1.9
49482	2.81		12.6
49483	0.45		12.4
49484	0.31		7.1
49485	0.42	0.51	4.0
49486	0.05		2.7
49488	0.02		<0.1
*0218	0.91		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 35 Years

Assay Certificate

8V-3063-RA9

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 20**
Attn: **Sue Deane**

Sep-19-08

We hereby certify the following assay of 6 core samples submitted Aug-27-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
49489	0.04	0.05	3.1
49490	0.68		11.0
49491	0.74		17.1
49492	0.64		8.1
49493	0.31		4.5
*0218	0.92		
*BLANK	<0.01		

Certified by _____



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3063RJ

Date : Sep-19-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/shipment 20

Attention : Sue Deane

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120118	1.1	1.49	107	103	<0.5	<5	3.59	4	17	40	105	4.60	<1	0.17	<10	0.95	2180	4	0.01	1	0.096	59	0.49	<5	6	54	<5	0.09	<10	<10	91	<10	396	2
120119	1.1	1.28	284	107	<0.5	<5	3.23	6	15	48	61	4.55	<1	0.15	<10	0.83	2138	3	0.01	2	0.086	64	1.24	<5	4	57	<5	0.05	<10	<10	77	<10	268	2
120120	2.3	1.53	232	86	<0.5	<5	2.51	11	12	55	33	5.19	<1	0.12	<10	1.25	2372	5	0.01	1	0.083	627	1.32	<5	4	55	<5	<0.01	<10	<10	80	10	1108	2
120121	11.7	0.67	725	26	<0.5	6	0.99	45	8	69	61	11.72	<1	0.06	<10	0.50	1115	<2	<0.01	1	0.061	524	>10.00	13	1	39	<5	<0.01	<10	14	33	42	4681	5
120122	2.1	1.13	320	103	<0.5	<5	2.88	7	10	92	40	3.70	<1	0.18	<10	0.73	1612	5	0.01	2	0.067	141	0.93	<5	3	64	<5	0.01	<10	<10	42	<10	229	2
120123	0.5	1.09	81	79	<0.5	<5	3.41	2	9	79	28	3.67	<1	0.19	<10	0.71	1568	4	0.01	2	0.071	21	1.02	<5	3	75	<5	0.01	<10	<10	41	<10	75	2
120124	0.7	1.15	86	145	<0.5	<5	2.89	2	11	116	61	3.99	<1	0.22	<10	0.75	1458	11	0.01	3	0.073	16	1.30	<5	3	70	<5	<0.01	<10	<10	42	<10	136	2
120125	160.6	0.85	185	215	<0.5	86	6.05	5	17	26	3907	3.95	3	0.16	<10	0.20	691	57	0.03	34	0.056	226	1.43	167	2	175	<5	0.07	<10	<10	24	<10	282	9
120126	1.5	0.98	94	105	<0.5	<5	1.64	3	11	91	83	4.45	<1	0.20	<10	0.62	1198	6	0.01	3	0.076	65	1.81	<5	3	45	<5	<0.01	<10	<10	39	<10	300	2
120127	0.9	0.90	89	87	<0.5	<5	1.73	2	11	110	73	4.17	<1	0.21	<10	0.70	1402	9	0.01	3	0.073	22	1.49	<5	3	66	<5	<0.01	<10	<10	34	<10	144	2
120128	1.1	0.37	201	83	<0.5	<5	2.90	4	17	109	45	4.01	<1	0.23	<10	0.54	1735	6	0.01	4	0.084	20	2.69	<5	4	229	<5	<0.01	<10	<10	16	<10	60	2
120129	7.9	0.64	205	107	<0.5	<5	3.93	7	18	105	156	5.29	<1	0.32	<10	0.65	1990	7	0.01	4	0.103	39	3.19	<5	5	284	<5	<0.01	<10	<10	30	<10	464	2
120130	1.4	1.14	144	107	<0.5	<5	4.54	3	17	71	63	4.67	<1	0.26	<10	0.63	2478	3	0.01	3	0.096	53	1.39	<5	5	127	<5	<0.01	<10	<10	64	<10	136	2
120131	0.2	1.22	51	103	<0.5	<5	2.96	1	9	115	19	3.90	<1	0.21	<10	0.79	1545	4	0.01	3	0.079	23	0.64	<5	4	76	<5	<0.01	<10	<10	49	<10	107	2
120132	1.0	1.11	126	106	<0.5	<5	3.12	4	9	96	41	3.93	<1	0.20	<10	0.76	1673	2	0.01	2	0.076	236	1.39	<5	3	82	<5	<0.01	<10	<10	46	<10	286	2
120133	0.4	1.10	106	101	<0.5	<5	2.86	3	9	118	35	3.91	<1	0.20	<10	0.76	1597	4	0.01	3	0.075	125	1.47	<5	3	76	<5	<0.01	<10	<10	46	<10	242	2
120134	5.4	0.52	233	22	<0.5	9	0.69	7	10	100	102	15.53	<1	0.19	<10	0.22	588	<2	<0.01	1	0.092	111	>10.00	35	1	26	<5	<0.01	<10	20	28	<10	598	8
120135	1.9	0.97	47	73	<0.5	<5	2.60	1	13	90	252	3.70	<1	0.21	<10	0.45	1214	7	0.01	2	0.074	12	1.00	<5	3	76	<5	0.01	<10	<10	58	<10	108	2
120136	1.4	1.08	100	73	<0.5	<5	3.35	2	13	80	194	4.06	<1	0.20	<10	0.60	1439	4	0.01	2	0.082	19	0.83	<5	4	121	<5	0.01	<10	<10	56	<10	112	2
120137	0.4	1.28	24	134	<0.5	<5	2.64	<1	14	74	111	4.30	<1	0.25	<10	0.69	1250	5	0.02	3	0.089	8	0.62	<5	5	83	<5	0.01	<10	<10	75	<10	90	2
120138	<0.2	0.75	<5	363	<0.5	<5	2.78	<1	8	53	11	2.08	<1	0.28	17	0.60	648	<2	0.03	5	0.070	8	0.27	<5	3	138	<5	<0.01	<10	<10	23	<10	44	5
120139	<0.2	0.76	<5	94	<0.5	<5	2.74	<1	8	50	16	2.15	<1	0.29	14	0.61	911	<2	0.02	4	0.072	16	0.43	<5	3	159	<5	<0.01	<10	<10	15	<10	58	3
120140	0.3	0.83	33	46	<0.5	<5	1.82	1	7	114	11	2.80	<1	0.18	<10	0.53	860	2	0.01	4	0.053	38	0.69	<5	2	89	6	<0.01	<10	<10	30	<10	64	2
120141	0.4	1.10	38	207	<0.5	<5	2.10	1	12	112	45	3.47	<1	0.18	<10	0.59	1007	5	0.02	4	0.060	6	0.97	<5	3	102	7	<0.01	<10	<10	51	<10	45	2
120142	<0.2	0.90	31	93	<0.5	<5	2.39	1	7	76	<1	2.86	<1	0.24	<10	0.52	1115	<2	0.01	1	0.073	24	0.88	<5	2	114	<5	<0.01	<10	<10	25	<10	100	2
120143	<0.2	0.43	43	291	<0.5	<5	4.98	1	7	121	<1	2.72	<1	0.20	<10	0.49	2000	4	0.01	2	0.059	10	0.95	<5	2	244	<5	<0.01	<10	<10	16	<10	31	1
120144	0.9	1.11	66	112	<0.5	<5	1.36	1	13	75	58	4.46	<1	0.24	<10	0.57	905	6	0.01	2	0.090	34	1.77	<5	3	54	<5	<0.01	<10	<10	47	<10	134	2
120145	0.2	1.13	54	84	<0.5	<5	2.12	1	10	110	12	3.85	<1	0.21	<10	0.56	1127	5	0.01	3	0.078	11	1.21	<5	3	64	<5	<0.01	<10	<10	51	<10	74	2
120146	0.2	0.48	56	152	<0.5	<5	1.65	1	7	53	<1	3.78	<1	0.28	<10	0.44	1007	2	0.01	1	0.088	15	2.30	<5	1	83	<5	<0.01	<10	<10	17	<10	59	3
120147	0.7	0.35	179	156	<0.5	<5	2.36	5	9	155	<1	3.65	<1	0.26	<10	0.55	1112	5	0.01	3	0.066	126	1.95	<5	2	125	<5	<0.01	<10	<10	17	<10	235	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3063RJ

Date : Sep-19-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/shipment 20

Attention : Sue Deane

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120148	<0.2	0.62	75	187	<0.5	<5	2.01	1	9	122	<1	3.33	<1	0.20	<10	0.69	1116	3	0.01	3	0.072	12	0.93	<5	3	85	<5	<0.01	<10	<10	31	<10	49	2
120149	<0.2	0.91	45	97	<0.5	<5	1.92	1	8	133	<1	3.20	<1	0.22	<10	0.66	1015	4	0.01	3	0.069	18	0.80	<5	3	61	<5	<0.01	<10	<10	33	<10	60	2
120150	<0.2	0.89	<5	246	<0.5	<5	0.41	<1	8	149	<1	2.00	<1	0.48	<10	0.57	570	<2	0.06	6	0.071	5	<0.01	<5	2	40	<5	0.11	<10	<10	38	<10	47	2
120151	1.4	0.51	129	84	<0.5	<5	2.05	2	9	150	<1	4.84	<1	0.23	<10	0.43	914	15	0.01	3	0.068	34	3.85	<5	2	74	<5	<0.01	<10	<10	18	<10	59	3
120152	0.6	0.50	115	79	<0.5	<5	4.45	2	11	85	8	3.09	<1	0.26	<10	0.45	1550	2	0.01	4	0.075	14	1.36	<5	3	152	<5	<0.01	<10	<10	18	<10	75	2
120153	<0.2	0.90	22	84	<0.5	<5	8.73	1	6	100	<1	2.75	<1	0.23	<10	0.58	2101	3	0.01	2	0.067	13	0.32	<5	3	570	<5	<0.01	<10	<10	21	<10	73	1
120154	1.8	0.97	101	58	<0.5	<5	5.35	5	7	71	<1	3.55	<1	0.19	<10	0.55	1611	<2	0.01	1	0.073	400	1.39	<5	2	148	<5	<0.01	<10	<10	26	<10	430	2
120155	<0.2	1.21	82	192	<0.5	<5	4.65	2	7	83	<1	3.56	<1	0.20	<10	0.70	1952	4	0.02	2	0.078	50	0.92	<5	3	137	<5	<0.01	<10	<10	35	<10	103	2
120156	<0.2	1.13	49	64	<0.5	<5	6.17	2	7	55	<1	3.33	<1	0.22	<10	0.60	1801	2	0.01	1	0.072	30	0.88	<5	3	150	<5	<0.01	<10	<10	29	<10	241	2
120157	<0.2	1.11	19	104	<0.5	<5	3.70	<1	7	84	<1	2.97	<1	0.20	<10	0.58	1414	3	0.02	1	0.076	7	0.46	<5	3	94	<5	<0.01	<10	<10	34	<10	85	2
120158	<0.2	1.00	40	90	<0.5	<5	3.17	1	7	66	<1	2.68	<1	0.22	<10	0.48	1177	3	0.01	1	0.069	25	0.41	<5	2	81	<5	<0.01	<10	<10	27	<10	89	2
120159	0.3	0.79	39	95	<0.5	<5	0.78	2	8	137	<1	2.57	<1	0.23	<10	0.30	572	6	0.01	3	0.072	94	0.77	<5	2	36	<5	<0.01	<10	<10	19	<10	306	2
120160	0.2	0.92	43	83	<0.5	<5	1.90	1	8	85	<1	3.31	<1	0.19	<10	0.41	879	5	0.01	1	0.069	14	1.23	<5	2	71	<5	<0.01	<10	<10	26	<10	90	2
120161	<0.2	0.97	27	61	<0.5	<5	1.94	5	7	125	<1	3.07	<1	0.18	<10	0.46	831	4	0.02	2	0.067	61	0.84	<5	2	58	<5	<0.01	<10	<10	28	<10	657	2
120162	<0.2	1.21	23	193	<0.5	<5	1.64	<1	8	109	<1	3.31	<1	0.25	<10	0.53	858	5	0.02	2	0.081	14	0.36	<5	3	60	<5	<0.01	<10	<10	31	<10	100	2
120163	0.2	1.06	43	77	<0.5	<5	2.02	1	8	77	<1	3.45	<1	0.20	<10	0.56	1068	3	0.01	1	0.076	24	1.01	<5	2	87	<5	<0.01	<10	<10	30	<10	114	2
120164	1.2	0.97	81	99	<0.5	<5	1.11	4	9	113	10	3.82	<1	0.26	<10	0.42	701	5	0.01	2	0.081	297	1.99	<5	2	38	<5	<0.01	<10	<10	26	<10	353	2
120165	3.9	1.87	95	149	<0.5	<5	3.40	13	7	100	8	3.77	<1	0.19	<10	0.51	1462	5	0.01	1	0.065	650	2.30	<5	2	83	<5	<0.01	<10	<10	24	15	1471	2
120166	6.4	1.06	124	67	<0.5	<5	2.08	9	8	113	89	5.14	<1	0.18	<10	0.49	1294	5	0.01	1	0.059	971	3.06	<5	2	52	<5	<0.01	<10	<10	28	<10	833	3
120167	1.0	1.05	69	83	<0.5	<5	1.76	2	9	88	<1	3.59	<1	0.21	<10	0.45	1162	4	0.01	2	0.067	66	1.12	<5	2	48	<5	<0.01	<10	<10	28	<10	235	2
120168	8.2	0.75	179	107	<0.5	<5	4.99	39	11	64	105	4.45	<1	0.23	<10	0.46	1817	6	0.01	1	0.070	887	3.53	<5	2	134	<5	<0.01	<10	<10	24	41	3965	2
120169	2.2	0.65	177	86	<0.5	<5	3.54	4	13	45	122	3.70	<1	0.25	<10	0.36	1224	11	0.01	1	0.103	93	3.03	<5	2	130	<5	<0.01	<10	<10	25	<10	241	2
120170	2.5	0.43	173	122	<0.5	<5	4.45	4	14	51	132	4.48	<1	0.29	<10	0.55	1409	6	0.01	1	0.110	29	3.20	<5	2	191	<5	<0.01	<10	<10	21	<10	173	2
120171	3.3	0.65	176	111	<0.5	<5	5.26	5	16	42	65	4.78	<1	0.25	<10	0.48	1707	5	0.01	1	0.116	42	3.39	<5	3	180	<5	<0.01	<10	<10	32	<10	350	2
120172	2.6	0.56	219	108	<0.5	<5	4.68	5	15	56	36	4.74	<1	0.29	<10	0.41	1809	8	0.01	1	0.124	32	4.02	5	3	144	<5	<0.01	<10	<10	29	<10	181	2
120173	4.1	0.31	336	92	<0.5	<5	4.22	7	15	34	187	4.43	<1	0.19	<10	0.26	1236	5	0.01	1	0.110	26	4.89	<5	2	161	<5	<0.01	<10	<10	17	<10	160	2
120174	3.2	0.36	481	109	<0.5	<5	8.92	10	14	24	80	4.77	<1	0.20	<10	0.25	2519	4	0.01	1	0.100	55	4.95	<5	2	248	<5	<0.01	<10	<10	18	<10	206	2
120175	2.9	1.87	636	223	<0.5	179	10.34	12	51	184	445	6.99	9	0.21	14	0.41	1053	111	0.05	75	0.095	91	2.39	5	4	137	<5	0.15	<10	<10	53	29	95	19
120176	3.6	1.24	117	166	<0.5	<5	4.42	3	18	21	185	4.73	<1	0.27	<10	0.73	1956	17	0.02	1	0.129	24	1.88	<5	3	173	<5	<0.01	<10	<10	49	<10	217	2
120177	3.5	1.03	147	195	<0.5	<5	6.05	3	15	49	73	4.14	<1	0.41	<10	0.59	2045	10	0.01	2	0.111	31	2.37	<5	2	174	<5	<0.01	<10	<10	31	<10	126	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3063RJ

Date : Sep-19-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/shipment 20

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Attention : Sue Deane

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120178	1.8	0.88	47	184	<0.5	<5	0.79	1	10	60	63	3.35	<1	0.25	10	0.75	1017	8	0.02	1	0.096	21	0.70	<5	2	46	<5	<0.01	<10	<10	29	<10	133	2
120179	1.7	0.89	45	182	<0.5	<5	0.77	1	10	58	63	3.24	<1	0.25	10	0.74	990	8	0.02	1	0.094	22	0.68	<5	2	45	<5	<0.01	<10	<10	29	<10	132	2
120180	1.4	0.40	80	99	<0.5	<5	3.40	1	13	29	7	4.12	<1	0.27	<10	0.42	1228	6	0.01	2	0.106	31	3.42	<5	2	174	<5	<0.01	<10	<10	14	<10	94	2
120181	0.5	1.29	24	158	<0.5	<5	4.08	<1	13	33	<1	4.02	<1	0.41	<10	0.86	1632	<2	0.02	2	0.106	20	1.65	<5	3	211	<5	<0.01	<10	<10	35	<10	84	2
120182	<0.2	1.56	17	146	<0.5	<5	3.35	<1	14	24	<1	4.42	<1	0.42	<10	0.90	1584	<2	0.03	2	0.113	14	1.09	<5	3	157	<5	<0.01	<10	<10	41	<10	93	2
120183	<0.2	0.62	16	110	<0.5	<5	3.18	<1	11	25	<1	3.61	<1	0.29	<10	1.13	1350	<2	0.02	1	0.092	14	0.83	<5	2	242	<5	<0.01	<10	<10	25	<10	90	2
120184	<0.2	1.64	31	129	<0.5	<5	4.51	<1	14	22	<1	4.50	<1	0.35	10	1.04	1888	3	0.02	2	0.118	15	1.31	<5	3	234	<5	<0.01	<10	<10	44	<10	103	2
120185	0.2	0.58	105	116	<0.5	<5	3.68	2	14	24	<1	4.90	<1	0.37	<10	0.56	1346	<2	0.02	2	0.126	23	3.75	<5	2	201	<5	<0.01	<10	<10	17	<10	121	3
120186	5.7	1.86	39	197	<0.5	<5	0.91	3	15	56	3	4.77	<1	0.73	12	0.86	1152	3	0.03	3	0.118	146	1.97	<5	3	58	<5	<0.01	<10	<10	49	<10	438	3
120187	11.6	1.33	30	156	<0.5	<5	1.73	2	13	34	<1	4.31	<1	0.33	11	0.88	1528	2	0.02	2	0.110	78	1.01	<5	2	89	<5	<0.01	<10	<10	43	<10	355	2
120188	2.9	1.75	29	164	<0.5	<5	3.78	<1	14	20	<1	4.38	<1	0.37	12	0.93	1922	<2	0.03	2	0.117	27	0.74	<5	3	204	<5	<0.01	<10	<10	52	<10	120	2
120189	0.7	1.90	16	171	<0.5	<5	3.55	<1	14	23	<1	4.52	<1	0.34	12	1.05	1643	<2	0.03	2	0.119	21	0.65	<5	3	216	<5	<0.01	<10	<10	52	<10	105	2
120190	1.4	1.93	27	151	<0.5	<5	4.02	1	16	27	22	4.98	<1	0.32	<10	1.08	1637	6	0.03	2	0.117	41	1.58	<5	3	158	<5	<0.01	<10	<10	59	<10	168	3
120191	1.4	1.62	29	181	<0.5	<5	2.52	1	17	37	19	4.90	<1	0.32	<10	0.92	1292	8	0.03	3	0.119	40	1.94	<5	3	100	<5	<0.01	<10	<10	48	<10	123	3
120192	10.5	0.88	161	138	<0.5	<5	2.23	4	13	33	<1	4.64	<1	0.31	10	0.64	1370	7	0.02	2	0.106	128	2.80	<5	2	110	<5	<0.01	<10	<10	28	<10	327	3
120193	3.3	1.24	74	143	<0.5	<5	2.06	2	13	38	<1	4.36	<1	0.35	10	0.61	1393	4	0.02	2	0.112	57	2.63	<5	2	91	<5	<0.01	<10	<10	31	<10	153	3
120194	23.5	1.16	89	137	<0.5	<5	1.23	3	16	27	<1	4.58	<1	0.30	10	0.60	1208	2	0.02	2	0.113	113	3.06	<5	2	67	<5	<0.01	<10	<10	33	<10	330	3
120195	1.9	1.49	163	208	<0.5	<5	0.50	3	14	35	<1	4.18	<1	0.43	14	0.66	1142	2	0.02	2	0.120	32	1.73	6	2	31	<5	<0.01	<10	<10	39	<10	142	2
120196	2.1	1.42	91	182	<0.5	<5	1.27	2	13	26	<1	3.63	<1	0.38	11	0.72	1294	3	0.02	1	0.112	20	1.06	<5	2	90	<5	<0.01	<10	<10	37	<10	108	2
120197	2.1	0.58	316	56	<0.5	<5	0.40	6	15	44	<1	4.42	<1	0.31	<10	0.20	313	13	0.02	2	0.114	37	4.76	<5	1	30	<5	<0.01	<10	<10	13	<10	111	3
120198	23.2	1.43	34	135	<0.5	<5	0.83	2	14	14	<1	4.50	<1	0.26	10	0.93	1429	<2	0.02	1	0.117	93	1.86	<5	2	49	<5	<0.01	<10	<10	40	<10	360	2
120199	1.0	1.69	34	160	<0.5	<5	1.21	<1	13	36	<1	4.25	<1	0.31	11	1.01	1750	<2	0.03	2	0.111	16	1.06	<5	2	75	<5	<0.01	<10	<10	48	<10	96	2
120200	<0.2	0.93	<5	250	<0.5	<5	0.44	<1	9	82	<1	2.02	<1	0.47	<10	0.59	596	<2	0.05	4	0.076	5	<0.01	<5	2	43	<5	0.12	<10	<10	40	<10	54	2
120201	2.5	1.24	64	142	<0.5	<5	0.65	1	13	39	<1	4.15	<1	0.33	<10	0.69	1157	2	0.02	2	0.114	19	2.29	<5	2	35	<5	<0.01	<10	<10	31	<10	108	2
120202	9.6	0.33	307	61	<0.5	<5	0.33	6	12	82	<1	4.74	<1	0.24	<10	0.07	150	3	0.02	3	0.099	48	5.84	8	1	26	<5	<0.01	<10	<10	7	<10	132	3
120203	17.8	0.30	632	50	<0.5	<5	0.29	15	15	48	<1	5.61	<1	0.22	<10	0.09	159	2	0.02	3	0.110	140	6.84	26	1	22	<5	<0.01	<10	<10	8	<10	396	3
120204	24.3	0.45	248	52	<0.5	<5	0.39	6	16	59	<1	4.89	<1	0.32	<10	0.13	239	4	0.02	3	0.112	128	5.71	14	1	27	<5	<0.01	<10	<10	10	<10	252	3
120205	2.5	0.81	73	140	<0.5	<5	0.92	1	15	21	<1	4.57	<1	0.27	10	0.73	1370	3	0.02	2	0.128	16	1.68	<5	2	52	<5	<0.01	<10	<10	25	<10	117	2
120206	3.7	0.31	88	76	<0.5	<5	1.79	2	13	46	31	3.75	<1	0.23	<10	0.51	1081	5	0.01	4	0.092	43	2.66	<5	2	106	<5	<0.01	<10	<10	13	<10	108	2
120207	0.5	0.45	16	161	<0.5	<5	2.71	<1	12	34	27	3.98	<1	0.24	<10	0.84	1606	<2	0.02	3	0.098	18	1.50	<5	2	145	<5	<0.01	<10	<10	21	<10	105	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3063RJ

Date : Sep-19-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/shipment 20

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Attention : Sue Deane

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120208	2.9	0.93	16	130	<0.5	<5	3.26	<1	11	32	25	3.93	<1	0.25	<10	0.80	1632	<2	0.02	2	0.097	32	1.42	<5	2	136	<5	<0.01	<10	<10	29	<10	94	2
120209	1.1	1.15	660	68	<0.5	<5	3.14	13	15	48	25	4.37	<1	0.16	<10	0.96	2056	5	0.01	1	0.097	29	2.43	<5	4	89	<5	0.01	<10	<10	68	<10	155	2
120210	1.3	1.22	591	59	<0.5	<5	3.28	14	14	43	62	4.70	<1	0.20	<10	0.81	1969	5	0.01	1	0.095	73	2.43	<5	3	72	<5	0.01	<10	<10	63	<10	386	2
120211	1.2	1.41	181	63	<0.5	<5	4.03	4	15	33	78	4.86	<1	0.17	<10	0.84	2106	4	0.01	1	0.102	34	1.50	<5	5	82	<5	0.04	<10	<10	81	<10	293	2
120212	1.7	1.41	202	78	<0.5	<5	3.01	4	17	29	139	4.82	<1	0.24	<10	0.79	1719	8	0.01	1	0.112	15	1.15	<5	4	75	<5	0.03	<10	<10	65	<10	172	2
120213	3.0	0.46	875	93	<0.5	<5	2.84	18	15	46	71	3.92	<1	0.28	<10	0.53	1606	19	0.01	2	0.110	60	1.93	<5	4	204	<5	<0.01	<10	<10	20	<10	129	1
120214	2.3	0.69	1259	97	<0.5	<5	2.98	27	17	44	95	5.04	<1	0.25	<10	0.61	1738	4	0.01	2	0.108	49	2.37	<5	4	201	<5	<0.01	<10	<10	28	<10	243	2
120215	1.0	1.36	128	86	<0.5	<5	3.88	3	16	26	125	4.69	<1	0.20	<10	0.71	1690	5	0.02	1	0.105	14	1.08	<5	5	109	<5	0.04	<10	<10	81	<10	153	2
120216	1.6	1.45	976	104	<0.5	<5	3.70	20	17	40	126	4.89	<1	0.20	<10	0.85	1954	4	0.01	1	0.108	286	1.36	<5	5	91	<5	0.03	<10	<10	79	<10	299	2
120217	0.3	1.07	141	104	<0.5	<5	4.05	3	8	48	28	3.27	<1	0.27	<10	0.61	1658	<2	0.01	1	0.077	79	0.98	<5	2	77	<5	0.01	<10	<10	45	<10	124	2
120218	<0.2	1.10	54	92	<0.5	<5	3.20	1	7	50	5	3.12	<1	0.25	<10	0.67	1572	<2	0.01	1	0.078	47	0.59	<5	2	58	<5	0.01	<10	<10	41	<10	67	3
120219	<0.2	1.08	47	113	<0.5	<5	3.68	1	7	40	12	3.08	<1	0.25	<10	0.60	1611	<2	0.01	1	0.079	10	0.59	<5	2	121	<5	<0.01	<10	<10	35	<10	51	2
120220	1.6	1.35	93	75	<0.5	<5	3.93	2	18	32	206	4.89	<1	0.17	<10	0.71	1873	5	0.01	1	0.105	12	1.47	<5	5	91	<5	0.05	<10	<10	87	<10	113	2
120221	2.1	1.34	65	111	<0.5	<5	3.10	3	16	59	218	4.90	<1	0.28	<10	0.60	1637	4	0.01	2	0.108	42	1.56	<5	5	76	<5	0.02	<10	<10	74	<10	396	2
120222	0.8	0.84	45	73	<0.5	<5	2.83	1	12	45	51	4.07	<1	0.18	<10	0.53	1724	2	0.01	1	0.097	13	1.45	<5	3	188	<5	<0.01	<10	<10	30	<10	164	1
120223	1.1	1.20	55	79	<0.5	<5	3.13	3	15	54	95	4.42	<1	0.23	<10	0.53	1601	3	0.01	1	0.108	49	1.59	<5	3	106	<5	0.03	<10	<10	59	<10	379	2
120224	1.7	1.22	29	68	<0.5	<5	3.28	3	18	38	233	4.17	<1	0.16	<10	0.58	1467	4	0.01	1	0.114	12	1.11	<5	4	112	<5	0.12	<10	<10	65	<10	321	3
120225	<0.2	0.77	<5	251	<0.5	<5	0.41	<1	9	84	4	2.04	<1	0.39	<10	0.55	596	<2	0.04	5	0.068	4	<0.01	<5	2	36	<5	0.11	<10	<10	39	<10	57	2
120226	0.2	1.15	33	54	<0.5	<5	2.18	2	14	43	39	3.66	<1	0.17	<10	0.67	1277	2	0.01	1	0.095	13	1.12	<5	4	92	<5	0.09	<10	<10	44	<10	303	2
120227	1.8	1.35	32	58	<0.5	<5	2.44	1	21	33	214	4.80	<1	0.12	<10	0.65	1342	5	0.02	1	0.110	14	0.98	<5	5	86	<5	0.14	<10	<10	95	<10	168	3
120228	1.4	1.57	27	68	<0.5	<5	2.26	1	19	44	130	4.70	<1	0.18	<10	0.72	1264	7	0.03	1	0.117	13	0.88	<5	4	66	<5	0.11	<10	<10	99	<10	144	3
120229	1.9	1.63	35	93	<0.5	<5	4.59	1	16	45	133	4.43	<1	0.23	<10	0.85	1948	3	0.03	1	0.121	12	0.93	<5	5	114	<5	0.07	<10	<10	82	<10	185	3
120230	7.1	0.95	225	81	<0.5	<5	4.54	5	11	50	115	3.39	<1	0.24	<10	0.50	2287	16	0.01	1	0.096	171	2.05	<5	2	82	<5	0.01	<10	<10	37	<10	151	2
120231	1.1	1.49	129	95	<0.5	<5	4.70	3	15	33	15	3.96	<1	0.21	<10	0.94	3179	4	0.01	1	0.105	54	1.30	<5	4	124	<5	0.07	<10	<10	47	<10	146	3
120232	2.1	1.83	95	98	<0.5	<5	3.65	2	15	25	59	4.84	<1	0.30	<10	1.11	3870	4	0.01	1	0.123	70	1.62	<5	3	87	<5	0.09	<10	12	59	<10	205	2
120360	0.6	2.35	<5	63	<0.5	<5	1.78	<1	21	23	164	4.58	<1	0.19	<10	1.65	1286	10	0.04	<1	0.122	11	0.07	<5	5	49	<5	0.16	<10	<10	100	<10	265	3
120361	0.3	1.81	15	47	<0.5	<5	2.75	1	17	30	19	3.34	<1	0.14	<10	1.12	1204	67	0.04	<1	0.107	9	0.19	<5	3	78	<5	0.13	<10	<10	73	<10	188	6
120362	13.0	1.89	13	51	<0.5	<5	2.31	1	20	18	22	3.83	<1	0.18	<10	1.23	1105	33	0.03	<1	0.111	11	0.13	<5	4	72	<5	0.13	<10	<10	77	<10	229	3
120363	1.6	2.07	75	55	<0.5	<5	2.96	2	18	16	138	4.78	<1	0.22	<10	1.26	1419	30	0.03	<1	0.113	13	0.36	<5	4	59	<5	0.11	<10	<10	81	<10	289	3
120364	0.6	2.08	17	72	<0.5	<5	2.62	1	19	14	43	4.51	<1	0.24	<10	1.34	1410	20	0.03	<1	0.119	13	0.56	<5	5	61	<5	0.13	<10	<10	86	<10	266	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3063RJ

Date : Sep-19-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/shipment 20

Attention : Sue Deane

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139434	7.9	0.13	298	105	<0.5	<5	0.61	15	2	193	59	2.70	<1	0.09	<10	0.04	808	2	0.01	3	0.018	2714	0.83	<5	<1	24	<5	<0.01	<10	<10	5	15	1637	1
139435	7.2	1.29	453	58	<0.5	<5	1.01	29	7	84	<1	7.05	<1	0.15	<10	0.94	1929	3	0.01	1	0.064	924	4.57	<5	1	17	<5	0.01	<10	10	30	34	3260	3
139436	15.9	1.25	475	52	<0.5	<5	0.29	30	8	79	<1	7.29	<1	0.14	<10	0.80	1255	3	0.01	<1	0.075	1672	5.24	<5	2	6	<5	0.01	<10	<10	33	32	3109	3
139437	9.2	1.37	150	65	<0.5	<5	0.24	96	8	117	113	5.68	1	0.17	<10	0.77	1548	10	0.01	2	0.089	1008	2.58	<5	2	4	<5	0.01	<10	<10	38	142	>10000	3
139438	2.3	1.69	97	74	<0.5	<5	0.63	60	11	69	80	5.62	<1	0.18	<10	1.04	1704	<2	0.01	1	0.095	1399	1.93	<5	3	15	<5	0.01	<10	<10	47	85	8359	3
139439	0.8	1.39	42	82	<0.5	<5	0.87	5	9	147	<1	3.87	<1	0.18	<10	0.86	1575	4	0.02	3	0.076	266	0.45	<5	4	20	<5	<0.01	<10	<10	44	<10	860	2
139440	19.7	0.94	248	95	<0.5	<5	0.31	19	6	128	152	5.43	<1	0.18	<10	0.49	932	3	0.01	2	0.080	>10000	1.95	6	2	9	<5	0.01	<10	<10	38	19	1949	3
139441	136.6	0.61	1077	26	<0.5	7	0.09	100	11	202	723	13.05	<1	0.08	<10	0.38	557	2	0.01	1	0.052	>10000	>10.00	31	1	4	<5	<0.01	<10	16	22	99	9751	6
139442	34.0	0.83	414	41	<0.5	5	2.24	164	16	92	1268	10.23	<1	0.10	<10	0.51	1547	<2	<0.01	<1	0.055	2219	>10.00	<5	1	36	<5	<0.01	<10	14	27	216	>10000	5
139443	69.3	0.48	478	23	<0.5	5	4.57	218	48	78	4287	12.21	1	0.05	<10	0.31	2509	<2	<0.01	<1	0.042	>10000	>10.00	7	1	89	<5	<0.01	<10	18	14	253	>10000	5
139444	39.4	0.60	522	47	<0.5	5	3.36	113	15	102	759	9.17	<1	0.15	<10	0.30	1862	<2	<0.01	1	0.049	3569	8.99	<5	1	61	<5	<0.01	<10	13	15	141	>10000	4
139445	6.1	0.21	119	127	<0.5	<5	0.53	7	7	348	67	3.72	<1	0.13	<10	0.04	856	8	0.01	7	0.054	548	0.48	<5	1	13	<5	<0.01	<10	<10	7	<10	664	2
139446	3.1	0.35	99	112	<0.5	<5	0.60	1	3	90	16	2.45	<1	0.18	<10	0.13	639	<2	0.01	2	0.048	89	0.14	5	1	22	<5	<0.01	<10	<10	15	<10	42	2
139447	4.2	0.57	182	151	<0.5	<5	0.38	2	5	43	20	3.81	<1	0.26	<10	0.26	808	<2	0.01	2	0.110	269	0.57	5	1	22	<5	<0.01	<10	<10	23	<10	127	3
139448	5.0	0.22	343	157	<0.5	<5	<0.01	1	2	76	7	2.58	<1	0.23	<10	0.05	112	<2	0.01	2	0.072	46	0.28	8	1	6	<5	<0.01	<10	<10	10	<10	35	2
139449	4.9	0.37	280	212	<0.5	<5	0.04	1	3	66	7	3.16	1	0.28	<10	0.14	241	<2	0.01	2	0.093	50	0.68	6	1	12	<5	<0.01	<10	<10	16	<10	24	2
139450	0.3	2.48	71	70	<0.5	<5	0.48	2	15	40	10	5.39	<1	0.13	<10	1.85	1707	<2	0.01	3	0.136	5	1.06	<5	4	10	<5	<0.01	<10	<10	83	<10	122	4
139470	0.7	2.12	50	74	<0.5	<5	0.34	2	15	39	14	6.26	<1	0.14	<10	1.55	1411	<2	0.01	3	0.137	18	2.30	<5	4	8	<5	<0.01	<10	<10	77	<10	68	4
139471	0.5	2.42	46	70	<0.5	<5	0.70	2	14	34	12	5.35	<1	0.12	<10	1.86	1701	<2	0.01	3	0.139	6	1.14	<5	4	15	<5	<0.01	<10	<10	84	<10	62	4
139472	0.7	1.76	60	63	<0.5	<5	0.03	2	6	36	8	7.47	<1	0.11	<10	1.20	1057	<2	0.02	2	0.130	19	1.56	<5	3	5	<5	0.01	<10	<10	75	<10	33	5
139473	0.6	2.15	56	70	<0.5	<5	0.37	2	14	37	14	6.43	<1	0.12	<10	1.59	1865	<2	0.02	3	0.125	13	1.92	<5	4	8	<5	<0.01	<10	<10	79	<10	101	4
139474	0.5	2.01	46	84	<0.5	<5	0.25	2	12	33	13	6.09	1	0.14	<10	1.42	1607	<2	0.01	3	0.138	14	1.52	<5	3	5	<5	<0.01	<10	<10	65	<10	131	4
139475	0.3	2.06	25	78	<0.5	<5	0.26	2	6	35	12	5.80	<1	0.14	<10	1.51	1451	<2	0.01	2	0.146	6	0.69	<5	4	6	<5	0.01	<10	<10	71	<10	86	4
139476	0.5	1.94	38	75	<0.5	<5	0.25	2	7	36	11	6.15	<1	0.12	<10	1.39	1323	<2	0.01	2	0.131	7	0.56	<5	3	6	<5	<0.01	<10	<10	76	<10	59	4
PB08#7	0.3	0.52	15	31	0.5	<5	1.27	3	16	20	6	6.54	<1	0.32	12	0.11	257	<2	0.03	8	0.244	21	6.32	6	3	50	5	<0.01	<10	<10	25	<10	233	6
PB08#8	<0.2	0.66	8	54	<0.5	<5	0.29	2	12	21	7	5.88	<1	0.24	11	0.09	77	<2	0.03	6	0.217	16	3.66	<5	2	12	<5	<0.01	<10	<10	26	<10	74	5
PB08#9	<0.2	0.55	28	23	<0.5	<5	0.25	3	38	17	13	7.41	<1	0.33	12	0.07	136	9	0.02	29	0.166	39	7.28	5	2	19	<5	<0.01	<10	14	25	<10	167	7
PB08#10	<0.2	0.07	5	47	<0.5	<5	15.77	<1	5	65	1	0.82	<1	0.05	<10	0.11	919	<2	0.01	7	0.015	<2	0.11	<5	1	>10000	<5	<0.01	<10	<10	3	<10	25	1
PB08#11	<0.2	0.29	<5	35	<0.5	<5	1.84	2	10	45	4	6.40	<1	0.17	11	0.16	308	<2	0.04	5	0.139	16	5.79	7	4	98	<5	<0.01	<10	<10	21	<10	53	6
PB08#12	<0.2	0.52	5	14	<0.5	<5	0.35	4	8	42	<1	9.82	<1	0.18	10	0.12	80	2	0.03	7	0.132	19	9.13	<5	2	21	<5	<0.01	<10	18	27	11	71	8

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3063RJ

Date : Sep-19-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/shipment 20

Attention : Sue Deane

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
PB08#13	<0.2	0.48	14	75	<0.5	<5	1.46	2	19	40	7	3.68	1	0.20	19	0.16	141	2	0.04	10	0.335	13	2.83	5	2	113	<5	<0.01	<10	<10	18	<10	118	9
PB08#14	<0.2	0.29	31	28	<0.5	<5	1.92	4	44	32	23	9.05	1	0.15	<10	0.13	356	<2	0.02	18	0.086	34	8.54	8	3	81	<5	<0.01	<10	12	23	<10	276	10
PB08#15	0.2	0.37	21	111	<0.5	<5	0.03	1	5	46	3	2.79	1	0.21	18	0.05	91	4	0.02	16	0.058	17	2.34	<5	1	13	<5	<0.01	<10	<10	9	<10	39	5
PB08#16	<0.2	0.68	<5	43	0.5	<5	0.42	2	9	41	7	4.85	<1	0.28	17	0.13	91	2	0.03	6	0.152	17	3.53	<5	2	28	<5	<0.01	<10	12	25	<10	101	7
PB08#17	<0.2	1.31	29	166	<0.5	<5	1.51	1	14	47	<1	4.98	<1	0.19	<10	0.84	796	4	0.02	48	0.089	27	1.94	<5	2	91	<5	<0.01	<10	<10	26	<10	150	3
PB08#18	<0.2	0.70	28	106	<0.5	<5	2.23	1	12	120	<1	3.42	<1	0.18	<10	0.96	576	<2	0.01	61	0.079	46	0.04	<5	4	238	<5	<0.01	<10	<10	16	<10	111	2
PB08#19	5.2	0.87	36	98	<0.5	<5	0.12	3	9	160	100	4.05	<1	0.15	<10	0.44	365	<2	0.01	47	0.082	1203	0.34	<5	4	22	<5	<0.01	<10	<10	22	<10	791	2
PB08#20	<0.2	2.22	14	143	0.5	<5	0.91	1	21	102	36	4.81	<1	0.21	<10	1.33	352	<2	0.02	97	0.082	144	0.57	<5	3	93	<5	<0.01	<10	<10	44	<10	286	3
PB08#21	<0.2	1.30	9	90	<0.5	<5	8.81	<1	11	94	<1	3.36	<1	0.14	<10	1.16	1020	<2	0.01	57	0.054	30	0.25	<5	2	1467	<5	<0.01	<10	<10	26	<10	99	2
PB08#22	<0.2	0.76	49	97	<0.5	<5	6.81	1	11	65	<1	4.85	<1	0.18	<10	2.49	1036	<2	0.02	46	0.090	28	0.13	<5	4	749	<5	<0.01	<10	<10	19	<10	101	2
PB08#23	<0.2	1.44	56	120	0.6	<5	1.74	1	16	65	29	4.14	<1	0.23	<10	1.00	303	<2	0.02	87	0.077	21	0.26	<5	5	189	<5	<0.01	<10	<10	38	<10	136	2
PB08#24	0.6	2.28	88	112	<0.5	<5	0.35	1	19	19	<1	6.02	<1	0.25	10	1.05	1340	<2	0.02	2	0.184	49	0.53	<5	4	7	<5	<0.01	<10	<10	99	<10	158	4
PB08#25	<0.2	0.49	8	134	<0.5	<5	0.08	<1	5	41	<1	5.71	<1	0.17	16	0.12	149	<2	0.03	3	0.090	78	1.72	<5	2	10	6	<0.01	<10	<10	11	<10	102	4
49475	6.2	0.52	265	122	<0.5	<5	0.07	5	9	110	<1	5.07	<1	0.25	<10	0.19	216	<2	0.01	28	0.125	31	1.35	6	2	2	<5	<0.01	<10	<10	25	<10	57	3
49476	4.3	0.98	240	118	<0.5	<5	0.33	4	20	30	<1	6.51	<1	0.28	<10	0.58	966	<2	0.01	4	0.148	36	4.05	5	3	9	<5	<0.01	<10	<10	35	<10	128	3
49477	2.0	2.10	261	103	<0.5	<5	2.14	4	21	33	<1	6.64	<1	0.26	<10	1.70	2084	<2	0.01	2	0.153	18	3.82	<5	4	60	<5	<0.01	<10	<10	66	<10	131	3
49478	5.1	1.53	200	113	<0.5	<5	2.65	3	20	37	<1	6.18	<1	0.32	<10	1.10	2024	<2	0.01	2	0.150	23	5.09	6	3	156	<5	<0.01	<10	<10	47	<10	108	3
49479	2.3	1.67	118	107	<0.5	<5	2.16	2	22	34	<1	5.81	<1	0.28	<10	1.25	2112	<2	0.01	3	0.138	24	4.35	<5	3	69	<5	<0.01	<10	<10	48	<10	180	3
49480	1.7	2.22	98	112	<0.5	<5	3.26	1	19	32	<1	5.93	<1	0.27	<10	1.89	2731	<2	0.01	2	0.141	19	3.12	<5	4	167	<5	<0.01	<10	<10	67	<10	148	3
49481	1.9	2.59	122	136	<0.5	<5	0.38	3	23	12	10	7.27	<1	0.37	13	1.26	1431	<2	0.01	1	0.203	31	1.54	<5	4	7	<5	<0.01	<10	<10	108	<10	187	3
49482	12.6	1.92	619	153	<0.5	<5	0.33	13	17	24	14	6.04	<1	0.40	10	0.93	935	<2	0.01	1	0.171	64	2.08	7	4	7	<5	<0.01	<10	<10	73	<10	159	3
49483	12.4	0.95	334	127	<0.5	<5	0.21	6	19	153	<1	4.25	<1	0.27	<10	0.42	686	<2	0.01	8	0.111	47	2.13	6	2	9	<5	<0.01	<10	<10	34	<10	79	2
49484	7.1	1.15	348	220	<0.5	<5	0.23	7	15	115	<1	3.89	<1	0.30	<10	0.54	649	<2	0.01	4	0.129	40	1.07	<5	3	9	<5	<0.01	<10	<10	43	<10	70	2
49485	4.0	1.54	404	187	<0.5	<5	0.31	8	67	383	60	4.48	<1	0.33	<10	0.73	1070	2	0.01	136	0.124	41	0.78	<5	2	8	<5	<0.01	<10	<10	52	<10	106	2
49486	2.7	2.00	138	158	<0.5	<5	2.25	3	28	35	17	5.81	<1	0.35	<10	1.04	1657	<2	0.01	5	0.150	28	1.63	<5	2	61	<5	<0.01	<10	<10	56	<10	135	3
49488	<0.2	0.97	15	136	<0.5	<5	2.62	<1	12	54	<1	4.36	<1	0.19	19	0.43	565	<2	0.04	10	0.094	25	3.37	<5	4	65	<5	0.04	<10	<10	25	<10	135	6
49489	3.1	1.97	23	183	<0.5	<5	0.72	<1	3623	156	5590	4.95	3	0.26	11	0.95	1049	11	0.03	78	0.151	53	0.29	<5	5	34	<5	0.06	<10	<10	66	<10	138	3
49490	11.0	0.18	209	57	<0.5	<5	0.03	3	8	96	97	2.06	<1	0.15	<10	0.02	28	<2	0.01	13	0.031	152	1.70	10	1	3	<5	<0.01	<10	12	6	<10	309	1
49491	17.1	0.25	386	64	<0.5	<5	0.11	6	120	72	386	4.38	<1	0.21	<10	0.02	14	<2	0.01	5	0.064	213	4.62	20	1	4	<5	<0.01	<10	15	11	<10	582	3
49492	8.1	0.24	432	55	<0.5	<5	0.06	9	12	100	57	3.92	<1	0.16	<10	0.02	171	<2	0.01	8	0.061	280	3.14	10	1	4	<5	<0.01	<10	<10	9	<10	1180	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3063RJ

Date : Sep-19-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/shipment 20

Attention : Sue Deane

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
49493	4.5	0.80	241	86	0.5	<5	2.86	9	19	27	37	5.33	<1	0.36	<10	0.54	1877	<2	0.01	8	0.152	163	4.25	5	2	125	<5	<0.01	<10	<10	21	<10	787	4
Blank-Inhouse	<0.2	1.06	<5	277	0.6	<5	0.62	1	8	199	1	2.31	<1	0.58	<10	0.64	617	<2	0.11	8	0.086	6	0.03	<5	3	65	6	0.16	<10	<10	45	<10	60	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Signed: _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3081-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment #21**
Attn: **Sue Deane**

Sep-16-08

We hereby certify the following assay of 22 core samples submitted Aug-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120233	0.10	0.09	1.4
120234	0.17		1.2
120235	0.11		1.2
120236	0.23		1.1
120237	0.13		2.1
120238	0.16		1.9
120239	0.06		2.7
120240	0.13		2.6
120241	0.13		2.3
120242	0.12	0.13	2.6
120243	0.09		3.5
120244	0.08		1.6
120245	0.05		1.8
120246	0.07		1.6
120247	0.10		3.5
120248	0.12		<0.1
120249	0.10		1.3
120250	0.47		0.5
120251	0.11		1.5
120252	0.08	0.07	1.2
120253	0.14		1.5
120254	0.08		0.3
*0218	0.92		
*BLANK	<0.01		<0.1

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3081-RA2

Company: **Ascot Resources Ltd**
 Project: **Dilworth/Shipment #21**
 Attn: **Sue Deane**

Sep-16-08

We hereby certify the following assay of 22 core samples submitted Aug-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
120255	0.01	<0.01	0.2	
120256	<0.01		0.4	
120257	0.09		0.9	
120258	0.10		1.9	
120259	0.25		1.9	
120260	0.20		2.5	
120261	0.09		1.1	
120262	<0.01		0.2	
120263	0.20		1.4	
120264	0.11	0.11	1.4	
120265	0.52		3.4	
120266	0.35		4.1	
120267	<0.01		0.2	
120268	0.05		0.7	
120269	0.28		1.6	
120270	0.42		2.3	
120271	0.19		2.8	
120272	0.06		0.8	
120273	<0.01		0.7	
120274	<0.01	0.02	0.6	
120275	0.08		>200	739.2
120276	<0.01		1.0	
*0218	0.91			
*CCu-1c				131.1
*BLANK	<0.01		<0.1	<0.1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3081-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment #21**
Attn: **Sue Deane**

Sep-16-08

We hereby certify the following assay of 22 core samples submitted Aug-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120277	0.22	0.22	2.0
120278	0.63		2.2
120279	0.36		1.5
120280	0.30		3.8
120281	0.34		2.6
120282	0.24		1.6
120283	0.52		2.3
120284	0.51		1.8
120285	0.67		3.9
120286	0.91	0.84	3.6
120287	0.58		3.1
120288	0.34		3.3
120289	0.71		3.2
120290	0.79		2.8
120291	0.71		2.0
120292	0.79		1.8
120293	0.53		1.9
120294	0.21		1.8
120295	0.13		1.5
120296	0.41	0.47	2.5
120297	0.32		1.3
120298	0.33		1.2
*0218	0.92		
*BLANK	<0.01		<0.1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3081-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment #21**
Attn: **Sue Deane**

Sep-16-08

We hereby certify the following assay of 22 core samples submitted Aug-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120299	0.21	0.23	2.8
120300	<0.01		<0.1
120301	0.19		2.7
120302	0.37		2.9
120303	0.95		2.7
120304	0.67		2.1
120305	0.48		1.3
120306	0.53		1.3
120307	0.32		1.2
120308	0.27	0.25	3.0
120309	0.26		3.7
120310	0.29		2.0
120311	0.37		2.3
120312	0.34		1.0
120313	0.37		0.6
120314	0.42		0.7
120315	0.49		1.0
120316	0.39		1.2
120317	0.31		1.3
120318	0.23	0.25	1.3
120319	0.12		2.3
120320	0.27		8.0
*0218	0.92		
*BLANK	<0.01		<0.1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3081-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment #21**
Attn: **Sue Deane**

Sep-16-08

We hereby certify the following assay of 22 core samples submitted Aug-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120321	0.10	0.10	1.8
120322	0.18		6.6
120323	0.23		2.1
120324	0.26		1.8
120325	1.81		175
120326	0.17		1.7
120327	0.24		1.3
120328	0.25		0.9
120329	0.26		1.0
120330	0.26	0.22	1.2
120331	0.35		1.8
120332	0.24		2.8
120333	0.24		1.8
120334	0.41		18.8
120335	0.24		1.2
120336	0.32		1.0
120337	0.32		1.0
120338	0.27		0.9
120339	0.37		1.3
120340	0.35	0.33	1.2
120341	0.29		1.7
120342	0.41		3.9
*0218	0.90		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3081-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment #21**
Attn: **Sue Deane**

Sep-16-08

We hereby certify the following assay of 22 core samples submitted Aug-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120343	0.43	0.43	1.5
120344	0.20		0.4
120345	0.39		0.9
120346	0.24		2.0
120347	0.24		1.5
120348	0.18		1.2
120349	0.12		0.5
120350	0.01		<0.1
120351	0.03		<0.1
120352	0.01	<0.01	<0.1
120353	0.01		<0.1
120354	0.21		0.2
120355	0.28		1.1
120356	0.58		1.8
120357	0.38		1.7
120358	0.26		0.7
120359	0.34		1.9
120365	0.10		7.4
120366	0.26		10.3
120367	0.03	0.02	0.9
120368	0.02		0.1
120369	0.22		2.2
*0218	0.92		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3081-RA7

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment #21**
Attn: **Sue Deane**

Sep-16-08

We hereby certify the following assay of 22 core samples submitted Aug-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120370	0.05	0.03	0.7
120371	0.04		0.8
120372	0.14		4.2
120373	0.79		9.5
120374	3.54		52.7
120375	<0.01		<0.1
120376	1.57		72.5
120377	0.56		13.7
120378	0.35		11.1
120379	0.62	0.61	20.6
120380	0.52		17.3
120381	0.23		4.3
120382	0.06		1.7
120383	0.24		28.6
120384	0.07		4.8
120385	0.02		2.3
120386	0.04		0.9
49494	1.22		197
49495	8.18		72.1
49496	0.07	0.07	14.0
49497	0.20		14.3
Beach #1	0.01		<0.1
*0218	0.92		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3081-RA8

Company: **Ascot Resources Ltd**
Project: Dilworth/Shipment #21
Attn: Sue Deane

Sep-16-08

We hereby certify the following assay of 2 core samples
submitted Aug-28-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
Beach #2	0.03	<0.01	0.1
*0218	0.92		
*BLANK	<0.01		

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3081RJ

Date : Sep-16-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment #21

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120233	1.4	1.19	56	116	<0.5	<5	2.88	1	12	37	123	3.10	<1	0.20	<10	0.75	2535	2	0.01	2	769	65	0.95	<5	2	55	<5	0.06	<10	11	43	<10	149	1
120234	1.2	1.35	124	93	<0.5	<5	3.08	3	15	19	107	3.22	<1	0.21	<10	0.88	2487	12	0.01	2	858	23	0.80	<5	3	75	<5	0.07	<10	10	47	<10	174	1
120235	1.2	1.25	30	77	<0.5	<5	2.58	1	14	19	140	3.37	<1	0.21	<10	0.71	1447	6	0.01	1	914	10	0.84	<5	4	71	<5	0.09	<10	<10	59	<10	128	2
120236	1.1	0.81	399	76	<0.5	<5	3.26	7	10	24	100	3.06	<1	0.17	<10	0.46	1934	6	<0.01	1	757	53	1.88	<5	2	58	<5	0.01	<10	<10	36	<10	119	1
120237	2.1	1.27	362	84	<0.5	<5	2.88	7	13	18	162	3.86	<1	0.18	<10	0.74	2547	6	0.01	1	862	37	1.35	<5	2	79	<5	0.01	<10	12	49	<10	209	1
120238	1.9	0.82	166	76	<0.5	<5	2.05	3	11	31	188	3.28	<1	0.20	<10	0.53	2256	7	0.01	2	712	21	1.82	<5	2	77	<5	<0.01	<10	11	26	<10	148	1
120239	2.7	0.98	42	84	<0.5	<5	2.80	2	11	17	210	2.81	<1	0.21	<10	0.66	2206	4	0.01	2	819	136	0.79	<5	2	131	<5	<0.01	<10	<10	38	<10	268	1
120240	2.6	1.05	47	98	<0.5	<5	2.53	1	16	12	193	3.13	<1	0.23	<10	0.69	2068	10	0.01	3	858	66	0.82	<5	3	136	<5	<0.01	<10	<10	42	<10	170	1
120241	2.3	1.17	55	87	<0.5	<5	2.02	1	23	22	222	3.22	<1	0.25	<10	0.62	1991	8	0.01	5	800	15	0.87	<5	2	75	<5	<0.01	<10	<10	52	<10	166	1
120242	2.6	1.15	28	70	<0.5	<5	1.56	1	11	18	279	3.10	<1	0.22	<10	0.64	1865	3	0.01	2	734	32	0.84	<5	2	52	<5	<0.01	<10	<10	38	<10	137	1
120243	3.5	1.05	114	62	<0.5	<5	2.73	3	12	22	282	3.11	<1	0.20	<10	0.62	2018	12	0.01	2	756	190	1.31	<5	2	77	<5	<0.01	<10	<10	45	<10	343	1
120244	1.6	1.28	131	72	<0.5	<5	2.85	3	13	12	124	3.59	<1	0.18	<10	0.79	2175	5	0.01	2	840	19	1.12	<5	3	77	<5	0.03	<10	<10	58	<10	144	1
120245	1.8	1.27	72	72	<0.5	<5	2.43	1	13	21	158	3.63	<1	0.19	<10	0.77	1922	8	0.01	2	800	15	0.96	<5	3	69	<5	0.01	<10	<10	55	<10	122	1
120246	1.6	1.17	68	84	<0.5	<5	3.00	2	12	13	148	3.57	<1	0.20	<10	0.77	1918	6	0.01	2	831	22	1.06	<5	3	84	<5	0.02	<10	<10	56	<10	141	1
120247	3.5	0.44	66	114	<0.5	<5	4.09	3	9	24	180	2.70	<1	0.21	<10	0.42	2030	4	0.01	2	583	272	1.32	<5	2	139	<5	<0.01	<10	<10	16	<10	377	1
120248	<0.2	0.75	4137	17	<0.5	13	4.54	76	138	10	70	2.81	<1	0.03	<10	0.18	534	9	0.06	24	859	10	1.00	<5	1	70	<5	0.04	<10	<10	29	<10	77	6
120249	1.3	0.88	52	87	<0.5	<5	3.30	1	13	14	205	3.03	<1	0.26	<10	0.48	1617	4	0.01	2	746	13	0.87	<5	3	122	<5	<0.01	<10	<10	31	<10	91	1
120250	0.5	0.97	38	59	<0.5	<5	2.52	2	8	35	83	2.80	<1	0.18	<10	0.64	1250	3	0.01	1	656	28	0.85	<5	3	79	<5	<0.01	<10	<10	30	<10	232	1
120251	1.5	0.96	74	66	<0.5	<5	2.62	2	11	21	105	3.29	<1	0.19	<10	0.56	1546	2	0.01	2	717	135	1.57	<5	2	88	<5	<0.01	<10	<10	39	<10	154	1
120252	1.2	1.21	55	119	<0.5	<5	1.97	1	13	22	134	3.97	<1	0.24	<10	0.70	2023	2	0.01	2	837	18	1.31	<5	3	60	<5	<0.01	<10	<10	56	<10	95	1
120253	1.5	0.39	88	67	<0.5	<5	2.86	3	10	30	108	3.21	<1	0.19	<10	0.44	1552	3	0.01	2	638	224	1.55	<5	2	77	<5	<0.01	<10	<10	15	<10	343	1
120254	0.3	0.33	23	52	<0.5	<5	1.08	1	10	31	98	3.06	<1	0.23	<10	0.46	1154	3	0.01	2	775	24	0.56	<5	2	42	<5	<0.01	<10	<10	12	<10	113	1
120255	0.2	0.40	14	98	<0.5	<5	2.77	<1	12	25	11	2.34	<1	0.26	12	0.43	862	<2	0.01	3	925	14	0.26	<5	2	61	<5	<0.01	<10	<10	7	<10	79	3
120256	0.4	0.46	8	142	<0.5	<5	2.65	<1	9	26	10	2.40	<1	0.29	15	0.68	503	<2	0.02	3	997	19	0.18	<5	2	105	<5	<0.01	<10	<10	10	<10	58	5
120257	0.9	1.25	21	222	<0.5	<5	6.10	<1	11	41	148	3.89	<1	0.22	10	0.89	1790	14	0.01	2	958	10	0.38	<5	4	135	<5	0.01	<10	<10	44	<10	102	2
120258	1.9	2.14	39	196	<0.5	<5	3.39	2	18	45	313	5.51	<1	0.18	<10	1.60	1675	10	0.01	6	1401	63	0.74	<5	7	103	<5	0.02	<10	<10	86	<10	224	2
120259	1.9	2.07	1221	149	<0.5	<5	4.34	24	18	39	318	5.71	<1	0.22	<10	1.52	2100	12	0.02	5	1466	61	1.47	<5	9	81	<5	0.04	<10	<10	96	<10	232	3
120260	2.5	2.28	63	144	<0.5	<5	2.81	3	22	39	330	6.00	<1	0.24	<10	1.59	1685	7	0.02	4	1529	42	1.26	<5	11	61	<5	0.10	<10	<10	106	<10	247	3
120261	1.1	1.83	26	155	<0.5	<5	3.65	1	19	42	265	4.92	<1	0.20	<10	1.15	1438	21	0.03	6	1484	42	0.56	<5	11	90	<5	0.08	<10	<10	99	<10	188	3
120262	0.2	0.80	<5	1003	<0.5	<5	3.27	<1	8	31	21	2.00	<1	0.26	17	0.70	664	<2	0.02	5	810	5	0.13	<5	3	113	<5	<0.01	<10	<10	22	<10	48	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3081RJ

Date : Sep-16-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment #21

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120263	1.4	1.55	22	121	<0.5	<5	4.78	<1	20	34	223	4.58	<1	0.29	<10	1.23	1795	8	<0.01	7	1423	17	0.31	<5	7	180	<5	<0.01	<10	<10	51	<10	131	2
120264	1.4	1.77	21	134	<0.5	<5	3.90	1	23	33	246	5.01	<1	0.32	<10	1.24	1725	15	<0.01	7	1605	17	0.26	<5	7	161	<5	0.01	<10	<10	54	<10	193	2
120265	3.4	1.60	3742	109	<0.5	<5	3.07	73	22	29	310	5.67	<1	0.28	<10	0.99	1745	7	<0.01	7	1554	63	1.43	16	6	112	<5	<0.01	<10	<10	52	<10	295	2
120266	4.1	1.90	61	88	<0.5	<5	1.96	2	17	49	381	5.70	<1	0.21	<10	1.05	1515	14	<0.01	6	1294	30	1.01	<5	6	43	<5	0.01	<10	<10	78	<10	201	2
120267	0.2	0.77	12	547	<0.5	<5	2.06	<1	8	23	14	2.27	<1	0.24	18	0.55	448	<2	0.02	3	982	29	0.09	<5	2	78	<5	<0.01	<10	<10	20	<10	99	5
120268	0.7	1.19	17	94	<0.5	<5	3.25	1	12	25	45	4.18	<1	0.25	10	0.95	1511	2	0.01	2	1084	38	0.52	<5	3	89	<5	<0.01	<10	<10	42	<10	205	2
120269	1.6	0.50	41	119	0.5	<5	2.75	1	14	29	80	4.39	<1	0.25	<10	0.63	1432	11	<0.01	3	1035	40	1.21	<5	3	89	<5	<0.01	<10	<10	22	<10	178	2
120270	2.3	1.62	35	79	<0.5	<5	3.04	1	18	25	163	5.47	<1	0.19	<10	0.90	1654	15	0.01	2	1401	39	1.27	<5	5	121	<5	<0.01	<10	<10	82	<10	258	2
120271	2.8	1.43	129	118	<0.5	<5	5.49	9	19	29	138	5.03	<1	0.27	<10	0.88	2011	10	0.02	1	1149	300	2.61	<5	4	153	<5	0.01	<10	<10	58	<10	870	2
120272	0.8	1.31	56	241	<0.5	<5	8.60	2	12	22	61	4.45	<1	0.23	<10	0.68	2618	7	0.01	1	1022	29	1.56	<5	4	165	<5	0.01	<10	<10	44	<10	153	2
120273	0.7	0.93	<5	538	<0.5	<5	2.83	<1	8	43	7	1.97	<1	0.26	17	0.63	586	<2	0.02	5	776	10	0.03	<5	2	100	<5	<0.01	<10	<10	18	<10	71	4
120274	0.6	0.49	<5	164	<0.5	<5	3.75	<1	7	28	2	1.74	<1	0.23	14	0.74	770	<2	0.02	4	719	7	0.04	<5	2	209	<5	<0.01	<10	<10	10	<10	49	3
120275	>200.0	1.02	493	248	<0.5	149	0.67	18	9	336	7021	2.82	4	0.30	<10	0.63	349	482	0.08	13	451	994	1.34	1353	2	90	<5	0.05	<10	<10	30	<10	1029	3
120276	1.0	0.88	<5	632	<0.5	<5	3.57	<1	8	26	23	1.91	<1	0.24	15	0.70	670	3	0.02	5	786	6	0.13	<5	2	188	<5	<0.01	<10	<10	19	<10	56	3
120277	2.0	0.99	111	78	<0.5	<5	4.49	8	13	100	120	4.24	<1	0.30	<10	0.69	1608	14	0.02	4	850	413	2.32	<5	3	261	<5	<0.01	<10	<10	32	<10	738	2
120278	2.2	1.58	117	157	<0.5	<5	3.46	4	16	41	149	5.34	<1	0.27	<10	0.89	1820	41	0.02	2	1236	31	2.23	<5	4	145	<5	<0.01	<10	<10	57	<10	421	3
120279	1.5	0.57	219	47	<0.5	<5	12.63	5	10	76	48	4.17	<1	0.22	<10	0.30	2939	8	0.01	2	713	89	4.14	<5	2	230	<5	<0.01	<10	13	17	<10	159	1
120280	3.8	1.25	134	78	<0.5	<5	3.56	4	15	81	286	4.98	<1	0.27	<10	0.64	1774	9	0.02	4	1085	92	2.59	<5	3	139	<5	<0.01	<10	<10	58	<10	333	2
120281	2.6	1.74	318	93	<0.5	<5	3.24	7	19	31	168	6.39	<1	0.31	<10	0.96	2001	18	0.01	2	1409	36	3.03	<5	4	106	<5	<0.01	<10	11	66	<10	288	2
120282	1.6	0.99	336	112	<0.5	<5	3.88	7	12	85	79	4.53	<1	0.20	<10	0.67	1944	12	0.01	3	812	67	3.11	<5	2	108	<5	<0.01	<10	<10	43	<10	180	2
120283	2.3	2.10	262	112	<0.5	<5	3.36	5	16	17	191	5.70	<1	0.29	<10	1.29	2300	20	0.02	<1	1398	28	1.43	<5	4	112	<5	0.03	<10	11	77	<10	224	2
120284	1.8	1.99	60	113	<0.5	<5	4.52	2	16	26	197	5.25	<1	0.31	10	1.11	2436	12	0.02	<1	1376	63	0.92	<5	4	151	<5	0.10	<10	11	75	<10	337	2
120285	3.9	2.02	103	93	<0.5	<5	3.67	3	19	13	350	5.67	<1	0.27	<10	1.26	2285	21	0.02	<1	1348	18	1.39	<5	5	123	<5	0.14	<10	11	85	<10	283	2
120286	3.6	2.39	54	79	<0.5	<5	5.28	1	22	19	328	6.41	<1	0.21	<10	1.41	2196	21	0.02	1	1316	22	1.16	<5	8	239	<5	0.14	<10	<10	134	<10	285	3
120287	3.1	2.14	84	87	<0.5	<5	4.79	2	18	14	285	5.95	<1	0.26	10	1.30	2045	12	0.02	1	1457	17	1.50	<5	7	201	<5	0.10	<10	<10	111	<10	290	2
120288	3.3	1.36	266	95	<0.5	<5	4.67	6	16	38	212	5.16	<1	0.31	<10	0.76	1815	17	0.02	1	1273	26	3.23	<5	5	131	<5	0.12	<10	<10	67	<10	223	2
120289	3.2	0.90	370	95	<0.5	<5	5.90	8	12	25	150	4.51	<1	0.29	<10	0.50	1823	11	0.01	1	998	34	4.00	<5	3	170	<5	0.05	<10	<10	36	<10	212	2
120290	2.8	1.03	290	63	<0.5	<5	8.19	6	11	38	117	3.74	<1	0.25	<10	0.55	3049	18	0.01	1	843	45	2.11	<5	2	183	<5	0.03	<10	13	34	<10	193	1
120291	2.0	1.46	165	64	<0.5	<5	4.84	4	13	24	160	4.70	<1	0.22	<10	0.82	2534	17	0.02	1	1045	23	1.73	<5	3	100	<5	0.02	<10	11	57	<10	193	2
120292	1.8	2.05	45	88	<0.5	<5	2.71	4	18	36	228	5.48	<1	0.21	<10	1.24	1952	9	0.03	1	1261	19	0.75	<5	6	65	<5	0.09	<10	<10	116	<10	407	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3081RJ**

Date : Sep-16-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment #21

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120293	1.9	2.30	13	76	<0.5	<5	3.75	2	20	10	229	5.59	<1	0.12	<10	1.76	2062	12	0.03	<1	1413	31	0.62	<5	10	90	<5	0.20	<10	<10	167	<10	289	4
120294	1.8	1.71	67	61	<0.5	<5	5.14	3	14	28	168	4.81	<1	0.25	<10	1.05	1716	8	0.03	1	1235	48	1.71	<5	6	132	<5	0.11	<10	<10	88	<10	285	5
120295	1.5	1.95	18	82	<0.5	<5	3.39	2	17	11	292	5.02	<1	0.16	<10	1.22	1332	6	0.04	<1	1310	15	0.72	<5	7	107	<5	0.18	<10	<10	106	<10	245	5
120296	2.5	1.77	125	78	<0.5	<5	3.96	4	16	23	250	5.42	<1	0.30	<10	0.83	1875	10	0.03	1	1330	54	1.92	<5	6	87	<5	0.15	<10	<10	81	<10	327	3
120297	1.3	1.96	34	69	<0.5	<5	3.85	1	18	10	211	5.55	<1	0.20	<10	1.06	1641	7	0.04	<1	1346	32	1.09	<5	7	100	<5	0.16	<10	<10	106	<10	243	5
120298	1.2	2.08	25	74	<0.5	<5	3.78	1	19	21	234	5.75	<1	0.24	<10	1.01	1603	8	0.03	1	1316	17	0.83	<5	8	124	<5	0.16	<10	<10	123	<10	246	5
120299	2.8	1.61	92	68	<0.5	<5	5.71	2	19	18	215	5.58	<1	0.21	<10	0.80	2093	7	0.01	1	1389	46	1.95	<5	6	112	<5	0.08	<10	<10	90	<10	266	3
120300	<0.2	0.97	<5	299	<0.5	<5	0.56	<1	10	113	7	2.42	<1	0.44	<10	0.68	683	<2	0.05	6	884	8	0.02	<5	3	46	5	0.14	<10	<10	45	<10	68	2
120301	2.7	1.59	53	67	<0.5	<5	4.34	1	17	15	190	5.06	<1	0.16	<10	0.96	1686	5	0.01	1	1379	14	1.48	<5	6	90	<5	0.06	<10	<10	94	<10	222	4
120302	2.9	0.53	270	49	<0.5	<5	8.66	6	12	39	104	4.00	<1	0.21	<10	0.24	1658	8	<0.01	1	997	311	4.21	<5	2	183	<5	<0.01	<10	<10	19	<10	275	2
120303	2.7	0.22	659	37	<0.5	<5	8.05	14	7	53	49	2.96	<1	0.13	<10	0.08	1357	5	<0.01	1	530	109	3.53	<5	1	200	<5	<0.01	<10	<10	6	<10	267	1
120304	2.1	1.38	87	73	<0.5	<5	4.03	2	14	38	208	4.57	<1	0.17	<10	0.83	1516	17	0.01	2	1231	22	1.39	<5	4	96	<5	<0.01	<10	<10	64	<10	210	2
120305	1.3	1.65	37	84	<0.5	<5	3.68	1	15	26	141	5.11	<1	0.20	<10	1.00	1438	9	0.01	1	1258	30	0.99	<5	5	126	<5	0.01	<10	<10	69	<10	246	2
120306	1.3	1.43	46	74	<0.5	<5	3.74	2	17	29	114	5.32	<1	0.18	<10	1.11	1527	7	0.01	1	1273	96	0.80	<5	5	140	<5	<0.01	<10	<10	74	<10	293	2
120307	1.2	0.69	128	89	<0.5	<5	3.46	3	16	33	71	4.93	<1	0.26	<10	0.67	1443	4	<0.01	1	1221	33	2.31	<5	4	142	<5	<0.01	<10	<10	27	<10	174	2
120308	3.0	0.44	260	107	<0.5	<5	2.92	11	17	46	91	4.64	<1	0.26	<10	0.60	1315	5	0.01	1	1126	232	2.22	<5	4	194	<5	<0.01	<10	<10	14	<10	641	2
120309	3.7	0.63	46	86	<0.5	<5	2.52	10	14	30	265	4.84	<1	0.25	<10	0.67	1130	3	0.01	1	1222	607	1.20	<5	4	147	<5	<0.01	<10	<10	19	10	1085	2
120310	2.0	1.62	37	81	<0.5	<5	5.46	2	16	32	164	4.98	<1	0.14	<10	0.91	1768	4	0.01	1	1363	26	0.38	<5	7	173	<5	0.01	<10	<10	100	<10	253	2
120311	2.3	2.12	30	87	<0.5	<5	2.90	1	20	22	139	5.85	<1	0.16	<10	1.57	1515	2	0.01	1	1441	22	0.85	<5	8	59	<5	0.07	<10	<10	117	<10	186	3
120312	1.0	2.18	117	84	<0.5	<5	3.43	3	21	18	84	7.26	<1	0.09	<10	1.92	1629	<2	0.01	<1	1202	106	2.65	<5	9	87	<5	0.05	<10	<10	153	<10	287	3
120313	0.6	2.73	<5	90	<0.5	<5	3.47	<1	23	11	105	6.57	1	0.15	<10	2.31	1761	2	0.01	<1	1155	14	0.33	<5	10	88	<5	0.13	<10	<10	169	<10	215	3
120314	0.7	2.70	7	94	<0.5	<5	2.90	<1	21	15	108	6.09	<1	0.24	<10	2.30	1696	<2	0.01	<1	1315	16	0.37	<5	7	57	<5	0.10	<10	<10	131	<10	211	3
120315	1.0	2.83	19	109	<0.5	<5	2.90	<1	19	7	113	6.69	<1	0.27	<10	2.28	1680	<2	<0.01	<1	1315	16	0.61	<5	6	55	<5	0.04	<10	<10	115	<10	227	3
120316	1.2	2.19	88	89	<0.5	<5	3.71	2	19	20	105	6.73	<1	0.23	<10	1.61	1740	3	<0.01	<1	1118	17	2.66	<5	6	80	<5	0.01	<10	<10	106	<10	238	3
120317	1.3	2.28	150	186	<0.5	<5	3.72	3	20	7	107	6.38	<1	0.28	<10	1.51	1888	2	<0.01	<1	1234	18	1.18	<5	6	96	<5	0.01	<10	<10	109	<10	265	2
120318	1.3	1.98	1107	86	<0.5	<5	3.37	21	18	18	93	5.72	<1	0.23	<10	1.25	1738	3	0.01	1	1215	19	1.32	7	4	82	<5	<0.01	<10	<10	89	<10	190	2
120319	2.3	1.80	134	116	<0.5	<5	2.15	3	19	12	155	6.34	<1	0.21	<10	1.17	1358	3	<0.01	1	1370	21	2.56	<5	3	97	<5	<0.01	<10	<10	79	<10	196	3
120320	8.0	0.40	1168	32	<0.5	13	2.98	20	12	33	38	>15.00	<1	0.10	<10	0.21	787	<2	<0.01	<1	866	80	>5.00	13	1	85	<5	<0.01	<10	27	21	<10	93	9
120321	1.8	1.79	95	100	<0.5	<5	3.10	3	18	19	95	5.30	<1	0.26	<10	1.04	1487	4	0.01	1	1157	16	1.43	<5	4	109	<5	<0.01	<10	<10	76	<10	213	2
120322	6.6	1.36	181	102	<0.5	<5	3.86	4	18	28	112	5.55	<1	0.29	<10	0.78	1653	8	<0.01	1	1081	30	2.67	<5	3	103	<5	<0.01	<10	<10	56	<10	207	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3081RJ

Date : Sep-16-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment #21

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120323	2.1	1.91	45	130	<0.5	<5	3.90	1	16	17	176	5.28	<1	0.29	<10	1.05	1632	7	0.01	1	1080	13	0.80	<5	4	118	<5	<0.01	<10	<10	78	<10	203	1
120324	1.8	1.96	20	86	<0.5	<5	3.42	1	17	26	136	5.26	<1	0.19	<10	1.19	1453	6	0.02	1	1041	14	0.52	<5	5	121	<5	0.02	<10	<10	98	<10	176	2
120325	175.9	0.96	197	230	<0.5	100	5.99	6	19	26	3674	3.95	4	0.18	<10	0.20	721	61	0.02	38	601	250	1.53	178	2	204	<5	0.07	<10	<10	25	18	276	9
120326	1.7	2.06	13	86	<0.5	<5	3.00	1	22	12	204	5.53	<1	0.15	<10	1.26	1513	3	0.02	1	1135	11	0.46	<5	7	72	<5	0.14	<10	<10	123	<10	184	3
120327	1.3	1.83	10	99	<0.5	<5	2.09	1	19	23	130	4.75	<1	0.18	<10	1.04	1179	10	0.02	1	1110	29	0.36	<5	6	67	<5	0.12	<10	<10	97	<10	161	2
120328	0.9	1.94	19	105	<0.5	<5	2.67	1	20	14	98	4.98	<1	0.25	<10	1.07	1256	7	0.02	1	1187	12	0.51	<5	5	70	<5	0.10	<10	<10	91	<10	164	2
120329	1.0	1.89	<5	64	<0.5	<5	2.28	1	20	28	95	4.50	<1	0.14	<10	1.14	1305	8	0.02	1	1086	14	0.27	<5	4	83	<5	0.16	<10	<10	87	<10	202	3
120330	1.2	1.61	11	76	<0.5	<5	3.06	1	15	24	70	4.00	<1	0.19	<10	0.97	1531	3	0.02	2	955	38	0.41	<5	5	76	<5	0.12	<10	<10	63	<10	183	3
120331	1.8	1.82	33	120	<0.5	<5	4.12	2	17	21	136	4.75	<1	0.23	10	0.98	2172	8	0.01	1	1030	23	0.63	<5	5	102	<5	0.07	<10	<10	76	<10	194	2
120332	2.8	1.88	62	114	<0.5	<5	4.33	5	20	15	207	5.39	<1	0.28	<10	0.94	2331	5	0.01	<1	1136	17	1.17	<5	6	115	<5	0.07	<10	<10	98	<10	280	2
120333	1.8	1.60	224	108	<0.5	<5	3.93	6	15	31	119	4.39	<1	0.24	10	0.89	2055	5	0.02	1	991	16	0.90	<5	5	103	<5	0.07	<10	<10	76	<10	243	2
120334	18.8	0.94	188	89	<0.5	<5	5.00	8	11	29	54	5.00	<1	0.25	<10	0.54	1942	12	<0.01	1	797	272	3.82	<5	3	129	<5	<0.01	<10	10	29	<10	576	2
120335	1.2	0.82	85	377	<0.5	<5	3.38	3	11	36	76	3.93	<1	0.30	10	0.86	1586	12	0.01	1	908	31	0.49	<5	4	216	<5	<0.01	<10	<10	20	<10	189	1
120336	1.0	1.49	15	194	<0.5	<5	2.54	1	11	35	60	4.28	<1	0.29	12	0.98	1329	6	0.02	1	970	33	0.48	<5	5	111	<5	0.01	<10	<10	45	<10	172	2
120337	1.0	1.44	13	161	<0.5	<5	2.68	1	11	42	58	4.22	<1	0.29	12	0.87	1365	26	0.01	1	944	11	0.61	<5	5	88	<5	0.01	<10	<10	53	<10	186	1
120338	0.9	1.50	21	107	<0.5	<5	2.33	1	10	40	60	4.33	<1	0.22	11	0.84	1213	13	0.02	1	864	12	0.86	<5	5	71	<5	0.01	<10	<10	59	<10	155	2
120339	1.3	1.49	24	88	<0.5	<5	2.92	1	11	42	65	4.24	<1	0.23	12	0.84	1252	7	0.01	1	907	37	0.73	<5	4	110	<5	<0.01	<10	<10	52	<10	157	1
120340	1.2	1.37	49	128	<0.5	<5	2.68	1	10	41	67	4.08	<1	0.25	10	0.78	1331	6	0.01	1	874	15	1.17	<5	4	95	<5	<0.01	<10	<10	47	<10	149	1
120341	1.7	1.26	38	134	<0.5	<5	2.68	1	11	44	79	3.89	<1	0.28	11	0.78	1624	5	<0.01	1	942	15	1.16	<5	4	122	<5	<0.01	<10	<10	43	<10	150	1
120342	3.9	0.68	188	108	<0.5	<5	2.03	10	11	48	88	4.44	<1	0.26	<10	0.59	1292	12	<0.01	1	788	753	3.03	<5	3	133	<5	<0.01	<10	<10	22	<10	890	1
120343	1.5	1.09	48	91	<0.5	<5	3.67	4	10	41	99	3.84	<1	0.20	<10	0.75	1989	4	0.01	1	868	31	1.39	<5	3	118	<5	<0.01	<10	<10	42	<10	504	2
120344	0.4	1.09	51	185	<0.5	<5	2.32	1	11	57	38	4.33	<1	0.27	12	0.70	1346	3	0.01	1	971	13	1.84	<5	3	93	<5	<0.01	<10	<10	43	<10	139	2
120345	0.9	1.20	28	90	<0.5	<5	2.21	1	11	48	90	4.46	<1	0.20	10	0.76	1242	15	0.02	1	955	12	1.52	<5	4	76	<5	0.01	<10	<10	50	<10	188	2
120346	2.0	0.75	180	89	<0.5	<5	5.08	4	11	42	47	5.45	<1	0.25	<10	0.49	1753	8	0.01	1	960	123	>5.00	<5	3	196	<5	<0.01	<10	<10	26	<10	180	2
120347	1.5	0.97	106	171	<0.5	<5	3.88	3	13	51	119	4.43	<1	0.31	<10	0.75	1976	6	0.01	1	1115	36	1.71	<5	3	217	<5	<0.01	<10	<10	35	<10	225	2
120348	1.2	0.48	116	157	<0.5	<5	3.76	3	12	55	69	4.23	<1	0.33	10	0.65	1743	13	0.01	1	1047	35	2.71	<5	3	173	<5	<0.01	<10	<10	13	<10	193	2
120349	0.5	0.44	66	180	<0.5	<5	2.94	1	12	46	51	4.18	<1	0.32	10	0.70	1564	4	0.01	1	1040	32	1.83	<5	3	141	<5	<0.01	<10	<10	15	<10	131	2
120350	<0.2	1.01	<5	348	<0.5	<5	0.53	<1	12	130	3	2.42	<1	0.51	10	0.69	741	<2	0.06	7	846	8	0.02	<5	3	50	5	0.14	<10	<10	48	<10	72	2
120351	<0.2	0.46	5	204	<0.5	<5	2.72	<1	8	65	2	2.14	<1	0.35	19	0.71	586	<2	0.03	4	833	22	0.08	<5	2	155	<5	<0.01	<10	<10	11	<10	53	4
120352	<0.2	0.31	5	1259	<0.5	<5	3.10	<1	7	57	1	2.18	<1	0.29	14	0.84	526	<2	0.03	4	754	9	0.11	<5	2	211	<5	<0.01	<10	<10	6	<10	42	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3081RJ

Date : Sep-16-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment #21

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120353	<0.2	0.94	<5	1307	<0.5	<5	2.14	<1	9	57	7	2.29	<1	0.25	22	0.78	535	<2	0.04	5	784	29	0.07	<5	3	99	<5	0.01	<10	<10	31	<10	49	6
120354	0.2	1.97	6	220	<0.5	<5	4.43	<1	15	29	94	5.26	<1	0.32	10	1.04	1831	6	0.05	1	1271	26	0.33	<5	7	96	<5	0.01	<10	<10	105	<10	153	2
120355	1.1	1.88	13	108	<0.5	<5	3.60	1	17	35	186	5.10	<1	0.29	10	1.05	1751	11	0.03	1	1326	38	0.66	<5	6	130	<5	0.01	<10	<10	98	<10	207	2
120356	1.8	1.95	18	111	<0.5	<5	2.73	1	23	27	239	5.44	<1	0.17	<10	1.16	1919	21	0.04	<1	1232	46	0.79	<5	7	56	<5	0.13	<10	<10	121	<10	263	3
120357	1.7	1.59	36	83	<0.5	<5	5.77	1	21	24	278	4.93	<1	0.21	<10	0.78	1831	13	0.03	1	1186	22	1.25	<5	5	89	<5	0.03	<10	<10	82	<10	208	2
120358	0.7	1.73	26	86	<0.5	<5	3.48	2	20	21	224	5.45	<1	0.16	<10	0.88	1731	10	0.03	1	1167	20	0.87	<5	5	101	<5	0.08	<10	<10	97	<10	240	3
120359	1.9	2.05	9	97	<0.5	<5	3.98	1	23	18	310	5.71	<1	0.15	<10	1.27	2530	17	0.03	1	1328	18	0.39	<5	8	109	<5	0.07	<10	<10	141	<10	265	3
120365	7.4	2.20	168	204	<0.5	<5	0.35	3	16	23	18	5.68	<1	0.23	10	1.17	1094	<2	0.01	1	1486	54	1.48	8	3	11	<5	<0.01	<10	<10	42	<10	261	2
120366	10.3	1.85	227	86	<0.5	<5	0.66	4	20	20	21	7.15	<1	0.21	<10	0.98	985	<2	0.01	1	1534	64	4.67	11	3	28	<5	<0.01	<10	<10	33	<10	250	3
120367	0.9	2.56	42	122	<0.5	<5	1.47	<1	18	17	19	6.22	<1	0.18	<10	1.46	1483	<2	0.01	<1	1551	17	1.25	<5	3	52	<5	0.01	<10	<10	42	<10	164	3
120368	<0.2	2.90	18	131	<0.5	<5	3.25	<1	16	14	15	6.13	<1	0.18	12	1.66	1818	<2	0.01	<1	1574	7	0.38	<5	4	98	<5	0.01	<10	<10	45	<10	145	3
120369	2.2	2.60	109	145	<0.5	<5	1.70	2	15	28	16	6.29	<1	0.21	13	1.45	1487	<2	0.02	<1	1563	17	1.35	<5	4	48	<5	<0.01	<10	<10	43	<10	140	3
120370	0.7	2.75	68	185	<0.5	<5	1.98	1	15	18	24	5.96	<1	0.28	10	1.43	1504	<2	0.02	<1	1495	10	1.08	<5	4	54	<5	<0.01	<10	<10	43	<10	133	3
120371	0.8	2.52	50	169	<0.5	<5	1.69	1	15	12	17	5.68	<1	0.27	<10	1.28	1418	<2	0.02	<1	1481	13	1.10	<5	4	45	<5	<0.01	<10	<10	40	<10	137	2
120372	4.2	1.65	253	169	<0.5	<5	0.95	5	14	36	18	5.36	<1	0.34	<10	0.75	865	<2	0.02	1	1370	23	3.27	<5	3	29	<5	<0.01	<10	<10	25	<10	96	2
120373	9.5	0.97	150	122	<0.5	<5	7.24	4	10	30	31	4.07	<1	0.20	<10	0.48	1814	<2	0.01	1	838	59	3.10	6	3	293	<5	<0.01	<10	<10	14	<10	147	2
120374	52.7	0.67	342	74	<0.5	<5	1.08	14	11	99	67	5.33	1	0.21	<10	0.27	424	4	0.01	5	806	616	>5.00	24	1	37	<5	<0.01	<10	<10	12	11	1202	2
120375	<0.2	1.03	<5	270	<0.5	<5	0.58	<1	8	109	2	2.28	<1	0.51	<10	0.63	654	<2	0.07	7	759	5	0.01	<5	3	56	5	0.13	<10	<10	43	<10	58	2
120376	72.5	0.85	420	84	<0.5	<5	1.07	14	15	90	79	5.22	1	0.29	<10	0.30	497	2	0.01	3	979	367	4.89	23	2	35	<5	<0.01	<10	<10	16	<10	892	2
120377	13.7	1.13	278	176	<0.5	<5	1.85	6	13	67	34	4.30	<1	0.27	<10	0.46	914	5	0.01	4	860	191	2.90	14	2	50	<5	<0.01	<10	<10	22	<10	220	2
120378	11.1	1.03	322	155	<0.5	<5	1.34	6	15	80	21	4.58	<1	0.25	11	0.40	804	2	0.01	3	992	47	3.44	12	2	41	<5	0.01	<10	<10	21	<10	115	2
120379	20.6	0.93	425	64	<0.5	<5	0.98	9	15	63	33	5.65	1	0.35	<10	0.26	568	5	0.01	3	983	68	>5.00	17	2	30	<5	0.01	<10	<10	19	<10	238	2
120380	17.3	1.44	265	205	<0.5	<5	0.27	6	15	86	32	5.70	<1	0.30	<10	0.68	1086	4	0.01	3	1114	50	2.34	7	3	9	<5	0.01	<10	<10	30	<10	291	2
120381	4.3	1.93	168	180	<0.5	<5	0.87	3	19	51	18	5.63	<1	0.28	<10	0.93	1307	2	0.01	2	1171	44	2.28	<5	3	27	<5	0.04	<10	<10	37	<10	147	3
120382	1.7	2.38	76	225	<0.5	<5	0.92	1	19	51	25	5.47	<1	0.32	<10	1.23	1530	3	0.01	2	1334	15	1.09	<5	4	31	<5	0.03	<10	<10	44	<10	131	2
120383	28.6	1.62	71	143	<0.5	<5	2.88	9	14	47	30	4.27	1	0.22	<10	0.84	1480	2	0.01	2	949	106	1.37	8	3	65	<5	0.01	<10	<10	31	<10	636	2
120384	4.8	1.84	168	185	<0.5	<5	0.61	4	18	44	25	5.09	<1	0.35	<10	0.81	1095	2	0.01	2	1270	22	2.02	<5	3	17	<5	0.02	<10	<10	34	<10	167	2
120385	2.3	2.49	158	260	<0.5	<5	0.58	3	20	18	15	5.92	<1	0.30	<10	1.35	1425	<2	0.01	1	1439	13	1.31	<5	4	17	<5	0.08	<10	<10	45	<10	125	3
120386	0.9	2.22	55	189	<0.5	<5	0.65	1	20	36	13	6.03	<1	0.30	<10	1.18	1216	<2	0.01	1	1367	11	2.42	<5	4	20	<5	0.06	<10	<10	47	<10	105	3
49494	197.6	0.21	52	96	<0.5	<5	<0.01	21	7	202	100	1.79	4	0.15	<10	0.02	57	15	0.01	8	233	1675	0.88	52	<1	2	<5	<0.01	<10	<10	5	28	3131	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment #21

Sample type:

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3081RJ

Date : Sep-16-08

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
49495	72.1	0.61	97	220	<0.5	<5	0.07	2	6	75	27	3.93	<1	0.34	<10	0.10	216	24	0.01	3	913	170	1.60	<5	1	3	<5	<0.01	<10	<10	12	<10	76	2
49496	14.0	0.69	31	191	<0.5	<5	0.11	1	9	64	35	4.01	<1	0.29	<10	0.18	224	7	0.01	3	1033	189	1.97	<5	1	4	<5	<0.01	<10	<10	16	<10	195	2
49497	14.3	0.36	56	146	<0.5	<5	0.01	1	6	227	46	4.68	<1	0.21	<10	0.05	88	6	0.01	6	585	388	1.47	<5	1	2	<5	<0.01	<10	<10	11	<10	168	2
Beach #1	<0.2	0.59	60	210	0.5	<5	0.36	1	39	62	9	2.93	<1	0.29	33	0.06	77	7	0.03	26	1124	33	0.41	<5	3	22	5	<0.01	<10	<10	8	<10	80	7
Beach #2	<0.2	0.45	46	144	<0.5	<5	0.27	1	26	83	2	1.83	1	0.24	23	0.04	48	7	0.03	15	975	23	0.21	6	2	18	<5	<0.01	<10	<10	8	<10	49	7

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

*Quality Assaying for over 25 Years***Geochemical Analysis Certificate****8V-3081-SG1**Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment #21**
Attn: **Sue Deane**

Sep-16-08

We hereby certify the following geochemical analysis of 19 soil samples submitted Aug-28-08

Sample Name	Au ppb
SL37	15
SL38	57
SL39	8
SL40	110
SL41	202
SL42	165
SL43	70
SL44	218
SL45	1624
SL46	280
SL47	177
SL48	<1
SL49	1
SL50	1
SL51	2
SL52	19
SL53	3
SL54	23
SL55	4
*0218	862
*BLANK	<1

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3081SJ**

Date : Sep-16-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment #21

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
SL37	0.5	1.52	78	49	<0.5	<5	0.23	2	17	52	56	3.74	1	0.03	<10	1.28	937	<2	0.01	18	859	46	0.07	<5	6	13	<5	0.04	<10	<10	82	<10	194	4
SL38	0.4	1.60	140	51	<0.5	<5	0.20	3	21	42	71	4.62	<1	0.03	<10	1.25	1195	<2	0.01	18	908	75	0.10	<5	5	11	<5	0.03	<10	<10	73	<10	235	5
SL39	0.2	1.00	30	57	<0.5	<5	0.16	1	13	15	13	4.12	<1	0.02	<10	0.61	480	<2	0.01	21	982	19	0.39	<5	2	14	<5	0.01	<10	<10	32	<10	86	4
SL40	4.6	0.88	98	118	<0.5	<5	0.13	2	13	12	34	3.85	<1	0.04	<10	0.57	828	<2	0.01	13	869	69	0.19	<5	2	9	<5	0.01	<10	<10	29	<10	114	3
SL41	2.2	1.30	101	139	<0.5	<5	0.20	3	20	21	55	4.85	<1	0.05	<10	0.84	1235	<2	0.01	17	1137	60	0.21	<5	4	13	<5	0.01	<10	<10	52	<10	193	4
SL42	1.4	1.76	248	69	0.6	<5	0.20	8	29	61	251	5.28	<1	0.03	<10	1.29	2066	10	0.01	20	935	153	0.18	5	8	10	<5	0.03	<10	<10	109	<10	842	5
SL43	3.0	1.38	168	71	<0.5	<5	0.19	4	18	28	100	4.60	<1	0.03	<10	0.97	1168	2	0.01	15	858	91	0.19	<5	5	11	<5	0.03	<10	<10	73	<10	336	4
SL44	3.2	1.53	422	77	<0.5	<5	0.16	6	20	36	151	5.21	<1	0.03	<10	1.03	1319	12	0.01	17	924	449	0.13	<5	5	11	<5	0.03	<10	<10	71	<10	546	5
SL45	7.9	1.94	197	119	0.6	<5	0.25	6	28	38	177	6.41	<1	0.06	<10	1.28	2760	121	0.01	18	1073	709	0.38	5	6	13	<5	0.03	<10	<10	87	<10	584	6
SL46	2.0	1.18	214	161	<0.5	<5	0.13	6	26	3	121	5.77	<1	0.09	<10	0.62	3070	20	0.01	5	1097	240	0.36	5	2	8	<5	0.01	<10	<10	43	<10	415	5
SL47	3.1	1.36	76	77	0.5	<5	0.15	2	16	16	57	4.57	<1	0.03	<10	0.77	933	<2	0.01	21	925	111	0.08	<5	2	12	<5	0.04	<10	<10	42	<10	193	5
SL48	<0.2	0.92	9	45	<0.5	<5	0.13	1	9	22	12	2.84	<1	0.02	<10	0.56	344	<2	0.01	33	801	9	0.06	<5	2	16	<5	0.01	<10	<10	25	<10	71	3
SL49	<0.2	1.00	9	42	<0.5	<5	0.14	1	9	24	12	2.97	1	0.02	<10	0.59	321	<2	0.01	33	826	8	0.05	<5	2	17	<5	0.01	<10	<10	26	<10	75	3
SL50	<0.2	1.24	8	46	<0.5	<5	0.19	2	13	18	35	5.11	<1	0.02	<10	0.70	540	<2	0.01	25	908	10	1.53	<5	2	15	<5	0.02	<10	<10	34	<10	80	5
SL51	<0.2	1.40	21	62	<0.5	<5	0.21	2	16	18	26	4.31	<1	0.02	<10	0.77	644	<2	0.01	26	971	11	0.33	<5	2	18	<5	0.02	<10	<10	32	<10	90	4
SL52	<0.2	1.94	47	113	0.7	<5	0.69	2	21	23	42	5.89	<1	0.05	<10	0.86	720	<2	0.02	32	1008	18	0.17	<5	4	71	<5	0.08	<10	<10	59	<10	108	6
SL53	<0.2	1.79	205	144	0.5	<5	0.21	2	22	14	99	6.23	<1	0.03	<10	0.75	1377	2	0.01	18	914	19	0.20	5	2	19	<5	0.03	<10	<10	51	<10	102	7
SL54	0.3	1.13	85	135	<0.5	<5	0.21	2	15	18	190	4.67	<1	0.03	<10	0.67	1229	12	0.01	23	987	40	0.45	6	3	24	<5	0.02	<10	<10	34	<10	143	5
SL55	<0.2	1.13	22	125	<0.5	<5	0.27	2	15	17	78	4.17	<1	0.05	11	0.65	893	<2	0.01	23	1135	22	0.16	<5	3	27	<5	0.01	<10	<10	33	<10	91	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Quality Assaying for over 35 Years

Assay Certificate

8V-3100-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 22**
Attn: **Sue Deane**

Sep-17-08

We hereby certify the following assay of 22 core samples submitted Sep-02-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
120387	0.02	0.02	1.4	
120388	0.08		1.2	
120389	0.05		0.9	
120390	0.17		1.6	
120391	0.05		2.8	
120392	0.20		4.2	
120393	0.05		3.3	
120394	0.11		4.3	
120395	0.01		0.8	
120396	0.01	0.01	0.8	
120397	0.01		0.8	
120398	0.01		1.2	
120399	0.01		5.9	
120400	1.40		>200	223.7
120401	0.01		2.5	
120402	0.04		1.1	
120403	<0.01		0.7	
120404	<0.01		0.4	
120405	0.01		0.4	
120406	0.01	0.02	0.5	
120407	<0.01		0.8	
120408	0.05		1.0	
*0218	0.91			
*CZn-3				0.689
*BLANK	<0.01			<0.001

Certified by _____

*Quality Assaying for over 35 Years***Assay Certificate****8V-3100-RA2**Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 22**
Attn: **Sue Deane****Sep-17-08**

We hereby certify the following assay of 22 core samples
submitted Sep-02-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120409	0.13	0.12	7.0
120410	0.19		2.3
120411	0.04		1.4
120412	0.06		1.4
120413	0.03		1.1
120414	0.02		0.7
120415	0.01		1.0
120416	0.01		1.1
120417	0.02		1.1
120418	0.07	0.08	1.6
120419	0.04		1.3
120420	0.10		2.7
120421	0.40		1.4
120422	0.09		3.6
120423	0.03		1.4
120424	0.08		1.6
120425	<0.01		<0.1
120426	0.13		1.9
120427	0.03		1.4
120428	0.02	0.01	1.3
120429	0.08		1.4
120430	0.03		1.8
*0218	0.92		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 35 Years

Assay Certificate

8V-3100-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 22**
Attn: **Sue Deane**

Sep-17-08

We hereby certify the following assay of 22 core samples submitted Sep-02-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120431	0.03	0.05	1.6
120432	0.02		1.1
120433	0.04		1.4
120434	0.24		3.7
120435	0.24		3.3
120436	0.15		3.2
120437	0.07		2.0
120438	0.12		1.8
120439	0.22		1.9
120440	0.06	0.04	2.7
120441	0.10		2.8
120442	0.18		4.7
120443	0.24		2.8
120444	0.08		1.7
120445	0.09		3.0
120446	0.04		0.9
120447	0.05		0.9
120448	0.03		0.6
120449	0.02		0.8
120450	1.75	1.76	190
120451	0.04		0.8
120452	0.03		0.7
*0218	0.91		
*BLANK	<0.01		

Certified by _____





Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 35 Years

Assay Certificate

8V-3100-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 22**
Attn: **Sue Deane**

Sep-17-08

We hereby certify the following assay of 22 core samples submitted Sep-02-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120453	0.02	0.01	0.7
120454	0.03		0.9
120455	0.03		1.0
120456	0.02		1.3
120457	0.06		1.1
120458	0.03		0.8
120459	0.07		1.0
120460	0.03		1.5
120461	0.05		1.4
120462	2.80	2.52	101
120463	0.27		2.9
120464	0.09		1.6
120465	0.13		1.3
120466	0.09		2.7
120467	0.08		1.1
120468	0.36		4.9
120469	0.12		2.8
120470	0.03		1.8
120471	0.13		9.9
120472	0.04	0.05	3.0
120473	0.07		3.2
120474	0.02		2.0
*0218	0.92		
*BLANK	<0.01		

Certified by _____



Quality Assaying for over 35 Years

Assay Certificate

8V-3100-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 22**
Attn: **Sue Deane**

Sep-17-08

We hereby certify the following assay of 22 core samples submitted Sep-02-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120475	<0.01	<0.01	<0.1
120476	0.01		0.8
120477	0.03		0.9
120478	0.04		1.1
120479	0.01		0.3
120480	0.01		0.3
120481	<0.01		0.3
120482	0.01		0.2
120483	0.01		0.5
120484	0.01	<0.01	<0.1
120485	0.01		0.3
120486	<0.01		0.4
120487	0.05		1.4
120488	0.01		0.2
120489	0.10		0.7
120490	0.12		1.1
120491	0.03		0.6
120492	0.06		1.0
120493	0.01		0.2
120494	0.01	<0.01	0.2
120495	0.02		<0.1
120496	0.03		<0.1
*0218	0.92		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 35 Years

Assay Certificate

8V-3100-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 22**
Attn: **Sue Deane**

Sep-17-08

We hereby certify the following assay of 22 core samples submitted Sep-02-08

Sample Name	Au g/tonne	Au-Check ppb	Ag g/tonne	Ag g/tonne
120497	0.01	0.01	0.3	
120498	0.01		<0.1	
120499	0.45		2.8	
120500	<0.01		<0.1	
120501	0.12		2.4	
120502	0.11		15.3	
120503	0.11		1.0	
120504	0.10		0.8	
120505	0.40		1.3	
120506	0.09	0.11	1.1	
120507	0.20		1.4	
120508	0.44		3.2	
120509	0.22		2.2	
120510	0.06		2.3	
120511	0.08		1.7	
120512	0.27		3.6	
139501	11.9		>200	454.8
139502	1.28		93.2	
139503	0.17		23.2	
139504	0.62	0.60	29.3	
139505	6.67		>200	412.0
139506	0.19		11.7	
*0218	0.91			
*CCu-1c				130.5
*BLANK	<0.01			<0.1

Certified by _____



Quality Assaying for over 35 Years

Assay Certificate

8V-3100-RA7

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 22**
Attn: **Sue Deane**

Sep-17-08

We hereby certify the following assay of 22 core samples submitted Sep-02-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
139507	1.75	1.74	105	
139508	0.06		1.6	
139509	0.08		2.7	
139510	0.02		0.7	
139511	0.04		0.6	
139512	0.35		2.5	
139513	0.04		1.6	
139514	0.26		2.6	
139515	0.11		1.9	
139516	0.03	0.03	0.8	
139517	0.05		0.7	
139518	0.03		0.8	
139519	0.14		1.7	
SD08-19	0.27		33.0	1.34
*0218	0.91			
*CCu-1c				3.92
*BLANK	<0.01			<0.1

Certified by _____





Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3100RJ

Date : Sep-17-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/Shipment 22

Attention : Sue Deane

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120387	1.4	2.65	31	204	<0.5	<5	0.61	<1	21	25	29	6.15	<1	0.25	<10	1.51	1507	<2	0.01	2	0.140	20	1.45	<5	4	18	<5	0.03	<10	<10	55	<10	138	3
120388	1.2	2.50	58	187	<0.5	<5	0.77	1	20	22	17	5.92	<1	0.23	<10	1.41	1525	<2	0.01	1	0.134	10	1.27	<5	4	23	<5	0.03	<10	<10	50	<10	121	2
120389	0.9	2.61	34	180	<0.5	<5	1.24	<1	21	17	22	6.24	<1	0.19	<10	1.51	1673	<2	<0.01	1	0.142	10	1.34	<5	4	33	<5	0.03	<10	10	50	<10	127	2
120390	1.6	2.77	42	172	<0.5	<5	0.71	<1	22	17	21	6.36	<1	0.21	<10	1.65	1792	<2	<0.01	1	0.140	9	1.13	<5	3	22	<5	0.03	<10	10	50	<10	142	2
120391	2.8	2.74	60	135	<0.5	<5	0.59	1	21	19	31	6.34	<1	0.18	<10	1.64	1806	<2	<0.01	1	0.134	9	1.11	<5	4	18	<5	0.01	<10	11	49	<10	151	2
120392	4.2	1.99	173	135	<0.5	<5	1.04	5	18	21	28	5.55	<1	0.23	<10	1.04	1456	<2	<0.01	1	0.117	11	2.19	<5	3	26	<5	0.02	<10	<10	36	<10	300	2
120393	3.3	1.49	139	182	<0.5	<5	0.33	3	17	18	21	4.58	<1	0.22	<10	0.72	1111	<2	<0.01	1	0.111	12	1.48	<5	2	10	<5	0.01	<10	<10	25	<10	97	1
120394	4.3	1.82	214	130	<0.5	<5	0.93	4	18	25	14	5.53	<1	0.23	<10	0.94	1265	2	<0.01	2	0.110	12	2.43	<5	3	25	<5	0.02	<10	<10	32	<10	90	2
120395	0.8	2.51	30	123	<0.5	<5	3.96	<1	17	10	12	5.03	<1	0.20	<10	1.71	1721	<2	<0.01	1	0.137	4	0.62	<5	4	96	<5	0.04	<10	<10	36	<10	105	2
120396	0.8	2.28	26	123	<0.5	<5	2.99	<1	20	13	16	5.65	<1	0.20	<10	1.36	1374	<2	<0.01	1	0.125	8	1.71	<5	3	81	<5	0.03	<10	<10	33	<10	115	2
120397	0.8	2.52	32	135	<0.5	<5	3.70	<1	16	10	21	5.26	<1	0.20	<10	1.45	1433	<2	<0.01	1	0.130	4	0.47	<5	3	113	<5	0.01	<10	<10	35	<10	128	2
120398	1.2	2.20	79	137	<0.5	<5	3.02	1	19	8	15	4.86	<1	0.21	<10	1.33	1257	<2	<0.01	1	0.130	6	0.86	<5	3	83	<5	0.02	<10	<10	31	<10	113	1
120399	5.9	1.56	71	144	<0.5	<5	1.31	1	17	30	15	4.43	<1	0.25	<10	0.81	835	5	<0.01	2	0.107	12	1.98	<5	2	33	<5	0.01	<10	<10	25	<10	96	1
120400	>200.0	0.84	1733	96	<0.5	61	4.55	39	62	23	2406	3.14	1	0.09	<10	0.24	856	115	0.04	25	0.076	426	0.73	320	2	142	<5	0.03	<10	<10	20	19	332	6
120401	2.5	2.26	72	144	<0.5	<5	1.83	1	18	11	20	5.05	<1	0.25	<10	1.27	1259	<2	<0.01	1	0.125	12	0.91	<5	3	42	<5	0.01	<10	<10	36	<10	114	2
120402	1.1	2.24	53	200	<0.5	<5	2.79	1	18	20	21	5.39	<1	0.23	<10	1.23	1418	<2	<0.01	1	0.123	7	1.15	<5	3	63	<5	0.01	<10	<10	32	<10	118	2
120403	0.7	2.08	24	171	<0.5	<5	4.51	<1	19	10	25	4.58	<1	0.23	<10	1.14	1408	<2	<0.01	1	0.122	3	0.60	<5	3	129	<5	0.04	<10	<10	27	<10	94	1
120404	0.4	2.16	8	1470	<0.5	<5	4.36	<1	16	14	22	4.68	<1	0.24	<10	1.12	1362	<2	<0.01	1	0.127	2	0.19	<5	3	865	<5	0.01	<10	<10	27	<10	101	1
120405	0.4	2.09	<5	1293	<0.5	<5	4.43	<1	16	8	19	4.81	<1	0.23	<10	1.04	1338	<2	<0.01	1	0.124	3	0.22	<5	3	469	<5	0.02	<10	<10	28	<10	101	1
120406	0.5	2.12	7	472	<0.5	<5	5.05	<1	17	10	11	4.94	<1	0.20	<10	1.04	1527	<2	<0.01	1	0.122	3	0.43	<5	3	221	<5	0.01	<10	<10	29	<10	102	1
120407	0.8	1.94	17	147	<0.5	<5	3.41	<1	16	10	13	4.66	<1	0.25	<10	0.99	1359	<2	<0.01	1	0.114	36	0.92	<5	3	123	<5	0.01	<10	<10	27	<10	125	1
120408	1.0	2.04	29	120	<0.5	<5	0.87	<1	20	19	21	6.04	<1	0.22	<10	1.04	1108	<2	<0.01	1	0.134	11	2.42	<5	3	31	<5	0.01	<10	<10	30	<10	120	2
120409	7.0	2.07	130	141	<0.5	<5	2.60	3	22	22	23	8.78	<1	0.26	<10	1.08	1242	<2	0.01	2	0.163	34	3.71	<5	3	60	<5	0.01	<10	<10	32	<10	188	3
120410	2.3	2.34	147	174	<0.5	<5	1.47	2	21	23	22	7.92	<1	0.27	<10	1.20	1304	<2	0.01	2	0.163	17	2.08	<5	3	45	<5	0.01	<10	<10	41	<10	131	2
120411	1.4	2.83	57	152	<0.5	<5	1.78	1	21	28	17	8.30	<1	0.25	<10	1.57	1533	2	0.01	2	0.148	8	1.10	<5	4	51	<5	0.01	<10	<10	45	<10	135	2
120412	1.4	2.96	113	134	<0.5	<5	4.19	2	21	19	17	8.66	<1	0.22	<10	1.68	1876	<2	0.01	2	0.163	7	1.17	<5	4	95	<5	0.01	<10	11	42	<10	146	3
120413	1.1	2.65	113	162	<0.5	<5	2.21	2	19	21	21	8.04	<1	0.25	10	1.47	1531	<2	0.01	1	0.152	6	1.21	<5	3	53	<5	0.01	<10	<10	37	<10	129	2
120414	0.7	2.74	144	153	<0.5	<5	1.33	2	22	19	18	7.84	<1	0.24	10	1.49	1562	<2	0.01	2	0.159	6	0.75	<5	4	40	<5	<0.01	<10	<10	44	<10	134	2
120415	1.0	2.83	87	159	<0.5	<5	1.72	1	20	20	19	8.57	<1	0.23	<10	1.62	1804	<2	0.01	1	0.161	6	1.29	<5	4	48	<5	<0.01	<10	10	44	<10	145	3
120416	1.1	2.62	93	145	<0.5	<5	2.25	1	22	14	23	8.41	<1	0.23	<10	1.54	1667	<2	0.02	1	0.159	7	1.69	<5	4	58	<5	0.01	<10	<10	43	<10	131	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3100RJ

Date : Sep-17-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/Shipment 22

Attention : Sue Deane

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120417	1.1	2.55	191	173	<0.5	<5	3.13	3	21	19	18	7.89	<1	0.26	<10	1.34	1726	<2	0.01	1	0.160	6	1.10	<5	4	72	<5	0.01	<10	<10	43	<10	126	2
120418	1.6	2.33	149	171	<0.5	<5	4.74	2	20	25	16	9.03	<1	0.23	<10	1.32	2168	<2	0.01	1	0.167	14	2.99	<5	4	123	<5	<0.01	<10	13	41	<10	128	3
120419	1.3	2.51	102	175	<0.5	<5	2.00	1	19	20	19	8.62	<1	0.23	<10	1.39	1574	<2	0.01	1	0.149	9	1.88	<5	3	59	<5	<0.01	<10	<10	38	<10	129	2
120420	2.7	2.15	241	148	<0.5	<5	5.46	4	19	25	20	8.50	<1	0.21	11	1.18	2010	<2	0.01	1	0.138	17	3.01	<5	3	116	<5	<0.01	<10	11	31	<10	111	2
120421	1.4	2.15	266	169	<0.5	<5	3.24	5	18	22	20	7.92	<1	0.23	<10	1.18	1608	<2	0.01	2	0.149	11	2.35	<5	3	83	<5	<0.01	<10	<10	36	<10	119	2
120422	3.6	2.29	470	159	<0.5	<5	1.46	9	21	25	20	8.85	<1	0.22	<10	1.28	1446	<2	0.01	2	0.138	15	2.57	5	3	63	<5	<0.01	<10	<10	39	<10	125	2
120423	1.4	2.84	247	201	<0.5	<5	2.93	4	22	19	23	8.78	<1	0.25	<10	1.60	1808	<2	0.01	2	0.180	7	1.22	<5	4	86	<5	<0.01	<10	10	47	<10	147	3
120424	1.6	2.67	211	191	<0.5	<5	3.23	4	20	22	30	8.51	<1	0.25	<10	1.55	1771	<2	0.01	2	0.185	8	1.54	<5	4	83	<5	<0.01	<10	10	44	<10	141	3
120425	<0.2	1.25	<5	333	<0.5	<5	0.75	<1	11	114	2	3.59	<1	0.56	10	0.88	764	<2	0.07	7	0.101	5	<0.01	<5	3	55	5	0.16	<10	<10	51	<10	78	2
120426	1.9	2.57	323	182	<0.5	<5	4.28	6	21	20	32	8.83	<1	0.24	<10	1.51	1866	<2	0.01	2	0.176	13	2.10	<5	4	109	<5	<0.01	<10	11	43	<10	137	3
120427	1.4	3.02	102	192	<0.5	<5	5.96	1	21	19	26	9.77	<1	0.26	<10	1.74	2019	<2	0.02	2	0.192	10	1.97	<5	4	139	<5	<0.01	<10	12	49	<10	141	3
120428	1.3	3.26	94	210	<0.5	<5	6.48	1	22	20	27	9.30	<1	0.27	<10	1.92	2226	<2	0.02	2	0.185	7	0.89	<5	5	158	<5	<0.01	<10	12	51	<10	156	3
120429	1.4	2.85	125	201	<0.5	<5	7.25	2	20	16	18	8.63	<1	0.27	<10	1.69	2246	<2	0.02	1	0.177	9	1.52	<5	4	168	<5	<0.01	<10	12	42	<10	134	2
120430	1.8	3.58	152	175	<0.5	<5	1.87	2	25	19	27	10.25	<1	0.23	10	2.37	1942	<2	0.01	2	0.180	10	1.18	<5	5	63	<5	<0.01	<10	11	64	<10	200	3
120431	1.6	2.86	187	490	<0.5	<5	0.91	3	25	35	33	7.64	<1	0.22	10	1.92	1656	<2	0.01	6	0.149	11	1.21	<5	4	48	<5	0.01	<10	<10	62	<10	152	3
120432	1.1	2.91	95	187	<0.5	<5	2.29	1	24	19	30	8.15	<1	0.26	10	1.87	1927	<2	0.01	4	0.160	13	1.21	<5	4	75	<5	0.01	<10	<10	56	<10	138	2
120433	1.4	2.47	339	176	<0.5	<5	2.06	6	21	29	28	7.71	<1	0.24	<10	1.46	1705	<2	0.01	4	0.131	12	1.59	<5	4	61	<5	0.02	<10	<10	47	<10	114	2
120434	3.7	1.75	435	158	<0.5	<5	1.04	10	21	25	22	7.34	<1	0.27	<10	0.92	1066	3	0.01	2	0.136	103	3.16	6	3	43	<5	<0.01	<10	<10	34	<10	454	2
120435	3.3	2.17	175	175	<0.5	<5	1.33	4	22	34	44	7.28	<1	0.27	<10	1.16	1459	2	0.01	2	0.167	72	1.84	<5	3	45	<5	<0.01	<10	<10	40	<10	266	2
120436	3.2	1.94	172	203	<0.5	<5	1.03	4	22	35	35	6.90	<1	0.22	<10	1.10	1287	6	0.01	2	0.126	124	1.92	<5	3	40	<5	<0.01	<10	<10	37	<10	210	2
120437	2.0	2.28	168	187	<0.5	<5	1.17	3	24	30	28	8.45	<1	0.30	<10	1.20	1390	11	0.01	2	0.173	31	2.90	<5	3	45	<5	<0.01	<10	<10	38	<10	153	3
120438	1.8	2.28	97	181	<0.5	<5	0.90	5	23	24	25	8.77	<1	0.28	10	1.24	1446	<2	0.01	3	0.160	48	3.13	<5	4	38	<5	<0.01	<10	<10	47	<10	706	3
120439	1.9	2.12	156	183	<0.5	<5	0.98	3	22	37	19	8.23	<1	0.29	<10	1.09	1300	<2	0.01	3	0.144	77	2.93	<5	3	40	<5	<0.01	<10	<10	44	<10	236	3
120440	2.7	2.20	676	173	<0.5	<5	1.52	13	20	23	23	8.68	<1	0.25	<10	1.17	1469	2	0.01	2	0.153	40	3.01	9	3	47	<5	0.01	<10	<10	41	<10	145	3
120441	2.8	2.14	176	181	<0.5	<5	1.89	4	22	34	33	7.49	<1	0.26	<10	1.14	1455	2	0.01	2	0.163	115	2.04	5	3	57	<5	0.01	<10	<10	39	<10	194	2
120442	4.7	2.58	206	139	<0.5	<5	2.08	12	21	22	24	8.97	<1	0.21	<10	1.39	1857	2	0.01	1	0.133	445	2.28	<5	3	55	<5	0.01	<10	10	45	10	958	3
120443	2.8	2.04	236	168	<0.5	<5	1.16	5	22	39	17	7.62	<1	0.27	<10	1.10	1241	3	0.01	2	0.139	41	2.74	5	3	45	<5	<0.01	<10	<10	39	<10	178	2
120444	1.7	2.08	93	115	<0.5	<5	1.83	4	22	15	24	9.23	<1	0.25	<10	1.17	1438	6	0.01	1	0.189	108	4.35	<5	3	52	<5	0.02	<10	<10	29	<10	385	3
120445	3.0	1.74	116	122	<0.5	<5	2.65	3	22	37	16	7.87	<1	0.22	<10	1.09	1522	4	0.01	2	0.133	469	3.99	<5	3	74	<5	0.03	<10	<10	37	<10	212	3
120446	0.9	1.70	46	100	<0.5	<5	3.65	1	22	20	13	8.79	<1	0.29	<10	1.06	1407	<2	0.02	2	0.172	30	5.60	<5	3	104	<5	0.03	<10	<10	31	<10	120	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3100RJ

Date : Sep-17-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/Shipment 22

Attention : Sue Deane

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120447	0.9	2.03	53	129	<0.5	<5	5.60	1	22	30	14	9.02	<1	0.27	<10	1.29	1958	3	0.02	2	0.149	22	4.57	<5	3	153	<5	0.02	<10	11	34	<10	117	3
120448	0.6	2.67	18	183	<0.5	<5	3.99	<1	20	16	21	8.20	<1	0.27	<10	1.65	2012	<2	0.01	1	0.162	13	1.96	<5	4	102	<5	0.01	<10	11	42	<10	143	2
120449	0.8	3.01	21	181	<0.5	<5	4.90	<1	20	24	25	8.07	<1	0.26	<10	1.80	2171	<2	0.01	1	0.159	6	0.79	<5	4	129	<5	0.01	<10	11	47	<10	130	2
120450	190.6	0.99	238	249	<0.5	105	7.38	7	21	30	3904	5.30	4	0.18	<10	0.25	759	83	0.03	41	0.075	270	1.61	253	2	203	<5	0.07	<10	<10	26	24	333	10
120451	0.8	2.87	37	197	<0.5	<5	1.85	<1	24	15	31	8.69	<1	0.27	<10	1.68	1697	<2	0.02	1	0.182	10	1.29	<5	4	54	<5	0.01	<10	<10	52	<10	134	3
120452	0.7	3.35	52	173	<0.5	<5	1.90	<1	22	31	21	9.89	<1	0.24	<10	2.04	1939	<2	0.01	1	0.153	7	1.16	<5	4	54	<5	0.02	<10	11	58	<10	150	3
120453	0.7	3.28	21	160	<0.5	<5	3.86	<1	20	13	20	6.84	<1	0.26	<10	1.95	2043	<2	<0.01	1	0.138	5	0.84	<5	5	131	<5	0.03	<10	12	52	<10	128	2
120454	0.9	3.19	25	168	<0.5	<5	3.38	<1	20	15	25	6.76	<1	0.28	<10	1.71	1959	<2	<0.01	1	0.147	6	0.63	<5	4	112	<5	0.01	<10	12	49	<10	127	2
120455	1.0	3.06	43	156	<0.5	<5	3.51	<1	23	10	20	6.64	<1	0.26	<10	1.68	1999	<2	<0.01	1	0.137	7	0.79	<5	4	112	<5	0.02	<10	12	46	<10	126	2
120456	1.3	2.92	25	181	<0.5	<5	3.97	<1	23	16	23	6.98	<1	0.26	<10	1.81	2317	<2	<0.01	1	0.149	7	1.25	<5	5	118	<5	0.01	<10	13	48	<10	145	2
120457	1.1	2.13	107	180	<0.5	<5	4.17	2	20	14	18	6.39	<1	0.31	<10	1.19	1943	<2	<0.01	1	0.135	16	2.44	<5	4	114	<5	0.03	<10	11	37	<10	200	2
120458	0.8	2.09	80	188	<0.5	<5	5.36	1	18	13	20	5.95	<1	0.30	<10	1.01	2161	<2	<0.01	1	0.140	7	2.13	<5	4	153	<5	0.01	<10	12	34	<10	115	2
120459	1.0	2.04	57	156	<0.5	<5	3.56	1	20	11	21	6.08	<1	0.32	<10	0.97	1817	<2	<0.01	1	0.149	15	2.46	<5	3	110	<5	0.02	<10	10	38	<10	136	2
120460	1.5	2.32	105	190	<0.5	<5	1.94	2	22	19	22	6.20	<1	0.34	<10	1.15	1615	<2	<0.01	2	0.149	18	2.03	<5	4	60	<5	0.01	<10	10	39	<10	118	2
120461	1.4	2.65	78	193	<0.5	<5	1.13	1	23	13	18	6.16	<1	0.31	<10	1.37	1694	<2	<0.01	1	0.139	12	1.00	<5	4	42	<5	0.01	<10	11	42	<10	148	2
120462	101.5	0.86	462	105	<0.5	<5	7.20	34	11	49	63	3.90	1	0.21	<10	0.39	1974	<2	<0.01	2	0.063	1020	3.11	30	3	241	<5	<0.01	<10	<10	14	31	3248	1
120463	2.9	1.70	171	157	<0.5	<5	4.39	4	18	29	23	4.80	<1	0.28	<10	0.78	1839	<2	<0.01	2	0.095	73	1.61	<5	4	138	<5	<0.01	<10	<10	28	<10	226	1
120464	1.6	2.78	113	202	<0.5	<5	1.40	2	25	21	21	6.61	<1	0.33	<10	1.40	1984	<2	<0.01	2	0.152	29	0.95	<5	5	54	<5	0.01	<10	11	48	<10	208	2
120465	1.3	1.83	82	194	<0.5	<5	3.87	2	17	23	26	4.55	<1	0.32	<10	0.90	2021	<2	<0.01	2	0.116	37	1.14	<5	4	161	<5	<0.01	<10	<10	34	<10	190	1
120466	2.7	1.81	128	185	<0.5	<5	1.41	25	16	34	86	4.53	1	0.31	10	0.96	1408	<2	<0.01	3	0.101	712	1.18	<5	3	69	<5	<0.01	<10	<10	50	22	2329	2
120467	1.1	1.79	96	201	<0.5	<5	0.70	3	18	23	27	4.39	<1	0.32	13	0.91	1427	<2	<0.01	2	0.107	25	0.82	<5	3	39	<5	<0.01	<10	<10	51	<10	248	2
120468	4.9	0.74	285	125	<0.5	<5	0.74	7	19	71	98	4.45	<1	0.31	<10	0.26	707	<2	<0.01	4	0.089	92	4.06	<5	2	52	<5	<0.01	<10	<10	20	<10	251	2
120469	2.8	1.70	204	122	<0.5	<5	1.06	4	20	17	40	5.55	<1	0.39	<10	0.90	1496	<2	<0.01	2	0.139	27	2.98	<5	2	79	<5	<0.01	<10	<10	43	<10	97	2
120470	1.8	1.94	79	185	<0.5	<5	1.12	2	18	21	42	5.26	<1	0.39	<10	1.00	1692	<2	<0.01	2	0.136	56	1.56	<5	2	61	<5	<0.01	<10	<10	50	<10	208	2
120471	9.9	0.97	106	67	<0.5	<5	1.30	90	15	52	584	4.97	3	0.24	<10	0.51	1087	<2	<0.01	2	0.080	2068	4.51	6	1	80	<5	<0.01	<10	<10	25	91	9288	2
120472	3.0	1.63	150	173	<0.5	<5	0.88	3	18	24	37	5.05	<1	0.40	<10	0.77	1349	<2	<0.01	2	0.132	34	2.14	<5	2	51	<5	<0.01	<10	<10	41	<10	135	2
120473	3.2	1.57	212	170	<0.5	<5	2.03	5	17	23	36	4.98	<1	0.41	<10	0.70	1814	<2	<0.01	2	0.124	43	2.21	<5	2	192	<5	<0.01	<10	<10	37	<10	173	1
120474	2.0	1.82	94	171	<0.5	<5	1.49	2	20	21	36	5.02	<1	0.46	11	0.86	1597	<2	<0.01	2	0.141	12	1.37	<5	2	103	<5	<0.01	<10	<10	39	<10	117	1
120475	<0.2	0.94	<5	218	0.7	<5	0.43	1	7	89	<1	1.91	<1	0.47	<10	0.57	527	<2	0.06	5	0.072	2	0.01	<5	2	56	5	0.13	<10	<10	38	<10	46	3
120476	0.8	1.28	93	125	<0.5	<5	5.28	2	14	14	28	3.80	<1	0.33	<10	0.66	3061	<2	0.01	3	0.113	13	1.05	6	1	790	<5	<0.01	<10	<10	29	<10	86	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3100RJ

Date : Sep-17-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/Shipment 22

Attention : Sue Deane

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120477	0.9	1.51	78	158	<0.5	<5	2.01	2	14	11	25	4.26	<1	0.30	<10	0.74	1402	<2	0.01	3	0.129	9	1.09	5	2	96	<5	<0.01	<10	<10	38	<10	80	3
120478	1.1	1.63	91	120	<0.5	<5	0.73	2	16	10	39	4.60	<1	0.33	<10	0.80	1102	<2	0.01	3	0.133	16	1.46	<5	1	51	<5	<0.01	<10	<10	42	<10	114	3
120479	0.3	1.76	63	137	<0.5	<5	1.44	2	15	7	30	4.55	<1	0.28	<10	0.94	1416	<2	0.01	2	0.136	7	0.94	<5	2	88	<5	<0.01	<10	<10	47	<10	86	3
120480	0.3	1.60	71	172	<0.5	<5	2.34	1	14	9	28	4.02	<1	0.30	<10	0.95	1551	<2	0.01	2	0.130	9	0.71	<5	2	176	<5	<0.01	<10	<10	41	<10	62	3
120481	0.3	1.72	47	107	<0.5	<5	2.56	1	15	8	27	4.40	<1	0.26	<10	1.00	1502	<2	0.02	3	0.131	10	1.17	<5	2	136	<5	<0.01	<10	<10	48	<10	64	3
120482	0.2	1.81	41	123	<0.5	<5	2.32	2	15	13	26	4.60	<1	0.22	<10	1.14	1587	<2	0.02	2	0.129	7	1.14	<5	2	179	<5	<0.01	<10	<10	51	<10	80	3
120483	0.5	1.89	42	104	<0.5	<5	1.36	2	18	5	35	5.13	<1	0.23	<10	1.21	1274	<2	0.02	2	0.139	9	1.62	<5	2	76	<5	0.01	<10	<10	58	<10	97	4
120484	<0.2	1.91	66	94	<0.5	<5	3.13	2	18	9	28	5.75	<1	0.23	<10	1.24	1844	<2	0.02	3	0.134	5	2.46	<5	2	154	<5	0.01	<10	<10	56	<10	94	4
120485	0.3	1.55	67	97	<0.5	<5	3.53	2	15	5	38	4.74	<1	0.22	<10	0.96	1679	<2	0.02	2	0.133	8	1.97	<5	2	182	<5	<0.01	<10	<10	47	<10	93	4
120486	0.4	1.91	79	114	<0.5	<5	2.27	2	16	9	28	4.86	<1	0.24	<10	1.10	1347	<2	0.02	2	0.132	8	0.98	<5	2	97	<5	<0.01	<10	<10	50	<10	71	3
120487	1.4	1.84	329	154	<0.5	<5	2.21	2	18	10	29	5.16	<1	0.40	<10	0.90	1166	<2	0.01	3	0.157	15	1.87	9	2	102	<5	0.01	<10	<10	41	<10	47	4
120488	0.2	1.85	42	136	<0.5	<5	3.80	1	14	9	27	4.18	<1	0.31	<10	0.97	1496	<2	0.02	2	0.137	3	0.52	<5	2	140	<5	0.01	<10	<10	38	<10	50	3
120489	0.7	1.18	102	118	<0.5	<5	4.84	1	13	15	25	3.48	<1	0.29	<10	0.55	1762	<2	0.01	2	0.108	12	1.54	<5	1	128	<5	0.01	<10	<10	25	<10	42	3
120490	1.1	0.87	164	118	<0.5	<5	3.50	1	13	26	15	3.54	<1	0.32	<10	0.38	1147	<2	0.01	2	0.111	27	2.64	<5	1	132	<5	0.01	<10	<10	19	<10	70	3
120491	0.6	1.49	98	138	<0.5	<5	4.20	2	16	12	34	4.23	<1	0.34	<10	0.82	1699	<2	0.01	2	0.138	11	1.99	<5	2	155	<5	<0.01	<10	<10	30	<10	83	3
120492	1.0	1.54	110	97	<0.5	<5	1.88	3	16	18	46	5.01	<1	0.31	<10	0.87	1256	<2	0.02	2	0.130	70	2.65	<5	2	76	<5	<0.01	<10	<10	41	<10	218	4
120493	0.2	1.80	40	86	<0.5	<5	1.77	2	15	7	31	4.61	<1	0.21	<10	1.13	1370	<2	0.02	2	0.134	11	1.16	<5	2	82	<5	0.01	<10	<10	58	<10	83	3
120494	0.2	1.73	39	115	<0.5	<5	2.08	2	15	12	43	4.36	<1	0.29	<10	1.04	1314	<2	0.02	2	0.140	14	1.19	<5	2	100	<5	0.01	<10	<10	50	<10	129	3
120495	<0.2	1.60	18	127	<0.5	<5	3.88	2	14	6	37	3.80	<1	0.22	<10	0.91	1509	<2	0.02	2	0.127	30	0.54	<5	2	175	<5	0.04	<10	<10	51	<10	124	3
120496	<0.2	1.45	62	96	<0.5	<5	5.30	2	14	10	24	4.00	<1	0.25	<10	0.84	1826	<2	0.02	2	0.126	13	1.36	<5	2	197	<5	0.02	<10	<10	40	<10	68	3
120497	0.3	1.69	33	96	<0.5	<5	4.42	1	15	6	23	4.29	<1	0.29	<10	0.90	1669	<2	0.02	2	0.141	7	0.83	<5	3	162	<5	0.01	<10	<10	53	<10	70	3
120498	<0.2	1.70	18	102	<0.5	<5	4.61	1	16	8	28	3.94	<1	0.26	<10	0.97	1624	<2	0.02	2	0.133	11	0.49	<5	3	163	<5	0.03	<10	<10	53	<10	77	3
120499	2.8	1.11	15	80	0.7	<5	2.28	2	15	87	325	2.88	<1	0.11	<10	0.98	960	23	0.02	14	0.133	18	0.13	<5	5	79	<5	0.13	<10	<10	78	<10	193	10
120500	<0.2	0.97	<5	223	0.7	<5	0.44	1	7	89	<1	1.96	<1	0.50	<10	0.60	552	<2	0.07	5	0.075	<2	0.01	<5	2	55	<5	0.13	<10	<10	38	<10	46	3
120501	2.4	1.30	22	48	0.5	<5	2.27	3	20	132	279	3.09	<1	0.08	<10	1.15	768	63	0.02	20	0.144	8	0.23	<5	5	134	<5	0.13	<10	<10	95	<10	196	6
120502	15.3	1.22	26	48	<0.5	<5	3.37	2	17	131	172	2.72	<1	0.07	<10	1.11	910	85	0.02	19	0.137	7	0.21	<5	5	92	<5	0.12	<10	<10	80	<10	146	7
120503	1.0	0.59	12	46	<0.5	<5	1.59	2	10	71	121	1.17	<1	0.07	<10	0.44	343	39	0.03	10	0.132	7	0.03	<5	2	77	<5	0.09	<10	<10	32	<10	113	6
120504	0.8	0.68	15	42	<0.5	<5	2.20	1	11	75	72	1.43	<1	0.08	<10	0.46	409	107	0.03	11	0.140	9	0.05	<5	2	94	<5	0.09	<10	<10	39	<10	100	7
120505	1.3	0.78	45	77	<0.5	<5	5.29	5	11	67	105	5.43	<1	0.08	<10	0.58	1282	37	0.02	8	0.077	12	0.45	<5	1	190	<5	0.04	<10	<10	39	<10	286	7
120506	1.1	0.96	25	39	<0.5	<5	2.90	2	15	104	132	2.57	<1	0.07	<10	0.70	751	70	0.02	18	0.140	6	0.17	<5	4	89	<5	0.10	<10	<10	69	<10	137	7

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3100RJ

Date : Sep-17-08

Sample type :

Ascot Resources Ltd

Project : Dilworth/Shipment 22

Attention : Sue Deane

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120507	1.4	1.04	20	57	0.8	<5	3.31	3	17	57	101	4.13	<1	0.07	<10	0.73	1047	10	0.03	10	0.114	6	0.33	<5	4	102	<5	0.16	<10	<10	61	<10	261	10
120508	3.2	0.62	43	27	<0.5	<5	2.15	4	16	61	260	2.78	<1	0.05	<10	0.26	618	26	0.01	10	0.070	15	0.70	<5	1	99	<5	0.05	<10	<10	36	<10	336	5
120509	2.2	0.65	19	41	<0.5	<5	1.56	1	11	101	245	1.39	<1	0.10	<10	0.33	413	72	0.02	12	0.138	13	0.08	<5	2	84	<5	0.11	<10	<10	47	<10	98	7
120510	2.3	1.38	44	48	0.6	<5	2.98	2	23	151	228	3.28	<1	0.08	<10	1.20	1025	44	0.02	24	0.154	11	0.42	<5	5	89	<5	0.15	<10	<10	90	<10	154	6
120511	1.7	1.02	63	45	0.5	<5	2.78	3	16	117	142	2.37	<1	0.07	<10	0.99	857	63	0.02	20	0.137	12	0.29	<5	3	84	<5	0.13	<10	<10	64	<10	207	5
120512	3.6	1.67	42	37	0.6	<5	2.99	3	23	150	273	3.78	<1	0.06	<10	1.69	1418	96	0.01	26	0.132	12	0.48	<5	6	71	<5	0.13	<10	<10	99	<10	211	5
139501	>200.0	0.70	643	26	<0.5	<5	0.21	52	8	78	131	7.50	5	0.26	<10	0.23	348	4	0.01	5	0.091	9806	5.74	74	1	20	<5	0.01	<10	<10	31	<10	8317	5
139502	93.2	1.30	875	56	<0.5	<5	0.23	17	19	38	88	6.96	1	0.25	<10	0.50	1019	<2	0.01	4	0.101	1231	4.58	33	2	9	<5	0.01	<10	<10	36	<10	2459	5
139503	23.2	1.47	561	98	<0.5	<5	0.19	4	17	49	46	5.37	<1	0.27	<10	0.61	1089	2	0.01	4	0.112	260	2.20	25	2	6	<5	0.01	<10	<10	40	<10	431	4
139504	29.3	0.67	1522	42	<0.5	<5	0.15	13	15	75	62	6.80	1	0.22	<10	0.23	880	5	0.01	4	0.072	563	5.48	45	1	5	<5	<0.01	<10	<10	27	<10	1653	5
139505	>200.0	0.50	955	24	<0.5	<5	0.28	33	10	89	86	8.32	5	0.21	<10	0.16	574	4	0.01	5	0.066	4930	7.01	52	1	14	<5	<0.01	<10	<10	24	<10	5180	6
139506	11.7	1.12	437	101	<0.5	<5	0.61	3	14	43	21	5.04	<1	0.28	<10	0.41	854	<2	0.01	4	0.109	193	2.67	16	2	23	<5	<0.01	<10	<10	37	<10	282	4
139507	105.1	1.37	633	71	<0.5	<5	0.87	11	15	61	44	6.99	1	0.22	<10	0.62	1170	<2	0.01	5	0.093	1603	3.65	26	2	25	<5	<0.01	<10	<10	45	<10	1518	5
139508	1.6	1.68	75	130	<0.5	<5	1.61	2	18	27	40	4.64	<1	0.26	<10	0.60	1293	<2	0.01	5	0.136	28	1.01	<5	2	44	<5	<0.01	<10	<10	53	<10	113	3
139509	2.7	1.61	91	105	<0.5	<5	2.27	2	23	40	69	5.18	<1	0.23	<10	0.81	1373	<2	0.01	6	0.121	39	2.00	<5	3	59	<5	0.01	<10	<10	52	<10	81	4
139510	0.7	2.64	51	108	<0.5	<5	1.79	2	33	22	70	6.37	<1	0.22	<10	1.58	1732	<2	0.01	8	0.151	11	1.10	<5	5	50	<5	0.02	<10	<10	91	<10	131	4
139511	0.6	2.30	36	151	<0.5	<5	3.26	3	28	31	61	5.83	<1	0.26	<10	1.16	1820	<2	0.01	7	0.140	6	1.06	<5	5	80	<5	0.01	<10	<10	88	<10	194	4
139512	2.5	0.74	349	124	<0.5	<5	0.31	2	12	53	28	4.82	<1	0.24	<10	0.23	585	2	0.01	4	0.099	48	1.67	7	2	9	<5	0.01	<10	<10	34	<10	33	3
139513	1.6	1.23	123	109	<0.5	<5	0.16	2	15	36	48	5.87	<1	0.26	<10	0.49	727	<2	0.01	5	0.134	60	1.88	6	3	6	<5	0.01	<10	<10	54	<10	71	4
139514	2.6	0.65	338	127	<0.5	<5	0.14	1	9	53	19	4.38	<1	0.24	<10	0.20	426	4	0.01	3	0.097	41	1.18	7	1	9	<5	<0.01	<10	<10	28	<10	49	3
139515	1.9	1.13	238	112	<0.5	<5	0.13	2	15	39	25	5.80	<1	0.27	<10	0.36	875	<2	0.01	3	0.141	38	1.81	7	2	4	<5	<0.01	<10	<10	39	<10	38	4
139516	0.8	1.29	108	112	<0.5	<5	0.17	2	15	27	26	5.20	<1	0.27	<10	0.47	698	<2	0.01	4	0.140	30	1.84	<5	2	5	<5	0.01	<10	<10	42	<10	45	4
139517	0.7	1.28	111	110	<0.5	<5	1.60	3	23	38	54	5.15	<1	0.27	<10	0.58	1344	<2	0.01	7	0.128	29	2.46	<5	3	38	<5	0.03	<10	<10	41	<10	186	4
139518	0.8	1.68	102	136	<0.5	<5	0.27	2	19	27	30	5.69	<1	0.31	15	0.60	926	<2	0.01	5	0.155	27	2.23	<5	3	7	<5	<0.01	<10	<10	49	<10	86	4
139519	1.7	1.28	151	122	<0.5	<5	0.89	2	17	41	33	4.21	<1	0.23	10	0.50	1257	4	0.01	5	0.110	133	1.28	<5	2	22	<5	<0.01	<10	<10	38	<10	138	3
SD08-19	33.0	0.21	216	77	<0.5	<5	12.14	115	16	56	3824	6.33	1	0.10	<10	0.10	4355	7	0.01	3	0.058	9001	6.51	24	2	245	<5	<0.01	<10	<10	14	<10	>10000	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3100-SG1

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 22**
Attn: **Sue Deane**

Sep-17-08

We *hereby certify* the following geochemical analysis of 20 samples submitted Feb-09-08

Sample Name	Au ppb
SL-56	8
SL-57	5
SL-58	<1
SL-59	2
SL-60	3
SL-61	2
SL-62	8
SL-63	37
SL-64	5
SL-65	9
SL-66	4
SL-67	4
SL-68	4
SL-69	3
SL-70	4
SL-71	2
SL-72	3
SL-73	8
SL-74	5
SL-75	3
*0218	884
*BLANK	<1

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3100SJ

Date : Sep-17-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 22

Sample type:

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
SL-56	<0.2	1.45	15	123	<0.5	<5	0.24	<1	18	29	27	5.32	<1	0.05	12	0.86	893	<2	0.01	40	1165	22	0.17	<5	4	19	<5	0.05	<10	<10	41	<10	127	3
SL-57	<0.2	1.68	14	100	<0.5	<5	0.20	<1	18	29	30	5.87	<1	0.05	13	0.96	835	2	0.01	35	1106	22	0.06	<5	3	14	<5	0.06	<10	<10	38	<10	110	4
SL-58	<0.2	1.44	8	103	<0.5	<5	0.18	<1	14	46	23	4.29	<1	0.05	10	0.89	551	<2	0.01	62	1003	16	0.04	<5	3	23	<5	0.03	<10	<10	39	<10	99	2
SL-59	<0.2	1.58	9	144	<0.5	<5	0.26	<1	19	42	41	5.16	<1	0.04	<10	1.01	743	<2	0.01	53	1233	21	0.59	<5	4	20	<5	0.05	<10	<10	43	<10	128	4
SL-60	<0.2	1.80	9	324	<0.5	<5	0.29	<1	21	28	29	5.29	<1	0.04	<10	0.95	1138	<2	0.01	34	1264	18	0.24	<5	3	21	<5	0.06	<10	<10	44	<10	147	4
SL-61	<0.2	1.74	10	228	<0.5	<5	0.27	<1	17	41	33	5.15	<1	0.04	<10	1.08	859	<2	0.01	51	1179	19	0.12	<5	4	25	<5	0.04	<10	<10	44	<10	120	3
SL-62	<0.2	1.79	7	106	<0.5	<5	0.22	<1	17	47	37	4.61	<1	0.04	<10	1.14	653	<2	0.01	63	1056	17	0.06	<5	4	18	<5	0.04	<10	<10	49	<10	118	4
SL-63	0.2	1.92	10	103	<0.5	<5	0.20	<1	19	39	73	5.12	<1	0.04	11	1.13	1183	<2	0.01	47	1136	19	0.06	<5	4	13	<5	0.04	<10	<10	54	<10	130	3
SL-64	<0.2	2.03	7	144	<0.5	<5	0.21	<1	21	37	39	5.59	<1	0.04	11	1.07	1254	<2	0.01	47	1176	18	0.11	<5	4	14	<5	0.04	<10	<10	51	<10	146	4
SL-65	0.4	1.24	48	76	<0.5	<5	0.08	<1	20	15	37	6.17	1	0.05	15	0.53	802	<2	0.01	17	1351	42	0.13	5	2	10	<5	0.03	<10	<10	35	<10	118	3
SL-66	<0.2	1.52	11	70	<0.5	<5	0.24	<1	17	49	26	4.35	<1	0.05	<10	1.07	498	<2	0.01	73	1094	22	0.15	<5	4	28	<5	0.03	<10	<10	43	<10	113	3
SL-67	<0.2	1.49	13	103	<0.5	<5	0.21	<1	16	34	24	4.27	<1	0.04	15	0.76	604	<2	0.01	58	819	29	0.01	<5	3	31	<5	0.04	<10	<10	46	<10	158	3
SL-68	<0.2	1.93	10	98	<0.5	<5	0.23	<1	21	72	36	4.96	<1	0.05	<10	1.21	556	<2	0.01	117	1172	17	0.05	<5	5	37	<5	0.02	<10	<10	46	<10	154	3
SL-69	<0.2	1.84	17	160	<0.5	<5	0.29	<1	27	40	46	5.23	<1	0.05	12	1.03	1161	<2	0.01	97	1089	21	0.02	<5	4	41	<5	0.05	<10	<10	54	<10	237	4
SL-70	<0.2	1.81	11	129	<0.5	<5	0.25	<1	23	41	37	4.61	<1	0.05	11	1.04	1009	<2	0.01	66	868	18	0.02	<5	4	38	<5	0.05	<10	<10	54	<10	171	3
SL-71	<0.2	1.97	9	98	<0.5	<5	0.19	<1	21	79	43	4.81	<1	0.05	<10	1.27	457	<2	0.01	121	1134	14	0.09	<5	5	32	<5	0.01	<10	<10	45	<10	134	3
SL-72	0.2	1.30	<5	127	<0.5	<5	0.33	<1	21	20	27	5.52	<1	0.04	16	0.66	1341	<2	0.01	27	1447	38	0.36	<5	4	25	<5	0.04	<10	<10	44	<10	221	3
SL-73	0.2	2.11	10	89	<0.5	<5	0.21	<1	27	65	46	5.59	<1	0.04	<10	1.25	982	<2	0.01	113	1142	21	0.08	<5	5	32	<5	0.04	<10	<10	54	<10	201	4
SL-74	0.2	1.98	20	118	<0.5	<5	0.17	<1	33	53	54	6.23	<1	0.04	<10	1.14	1140	<2	0.01	105	1155	20	0.05	<5	6	20	<5	0.04	<10	<10	62	<10	206	5
SL-75	<0.2	1.90	<5	221	<0.5	<5	0.33	<1	16	19	64	4.40	<1	0.04	10	1.15	1393	<2	0.01	23	1137	12	0.02	<5	4	21	<5	0.06	<10	<10	58	<10	139	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Quality Assaying for over 25 Years

Assay Certificate

8V-3190-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment23**
Attn: **Sue Deane**

Sep-15-08

We hereby certify the following assay of 22 core samples submitted May-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120513	0.69	0.76	4.3
120514	0.28		8.7
120515	0.49		6.7
120516	0.30		6.1
120517	0.18		3.6
120518	0.10		7.5
120519	0.07		4.9
120520	0.11		3.1
120521	0.08		3.0
120522	0.26	0.26	6.4
120523	0.64		11.4
120524	0.11		3.6
120525	0.44		0.5
120526	0.05		2.3
120527	0.04		2.9
120528	0.08		3.0
120529	0.13		3.8
120530	0.38		3.7
120531	0.32		4.1
120532	0.24	0.23	3.5
120533	0.16		2.7
120534	0.23		2.0
*0218	0.89		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3190-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment23**
Attn: **Sue Deane**

Sep-15-08

We hereby certify the following assay of 22 core samples submitted May-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120535	0.14	0.14	1.0
120536	0.23		1.0
120537	0.37		0.5
120538	0.55		1.2
120539	0.38		2.1
120540	0.33		1.3
120541	0.21		0.8
120542	0.54		1.7
120543	0.74		3.2
120544	0.32	0.30	1.3
120545	0.54		1.7
120546	0.19		2.1
120547	0.26		2.2
120548	0.51		2.3
120549	0.24		0.8
120550	0.01		<0.1
120551	0.12		2.3
120552	0.05		0.3
120553	0.14		0.2
120554	0.07	0.06	<0.1
120555	0.16		0.3
120556	0.11		1.2
*0218	0.92		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3190-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment23**
Attn: **Sue Deane**

Sep-15-08

We hereby certify the following assay of 22 core samples submitted May-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
120557	0.41	0.41	5.3	
120558	0.18		2.0	
120559	0.18		1.9	
120560	0.10		1.1	
120561	0.10		1.8	
120562	0.06		2.5	
120563	0.13		3.7	
120564	0.19		3.7	
120565	0.18		3.3	
120566	0.31	0.31	3.3	
120567	0.09		3.6	
120568	<0.01		0.1	
120569	0.13		3.2	
120570	0.28		2.5	
120571	0.25		3.8	
120572	0.13		4.0	
120573	0.12		3.5	
120574	0.10		3.8	
120575	1.84		180	
120576	0.17	0.16	2.8	
120577	0.24		5.1	
120578	0.33		11.4	1.89
*0218	0.90			
*CCu-1c				3.93
*BLANK	<0.01			<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3190-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment23**
Attn: **Sue Deane**

Sep-15-08

We hereby certify the following assay of 22 core samples submitted May-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
120579	0.33	0.30	6.0	
120580	0.21		4.9	1.07
120581	0.22		11.1	1.12
120582	0.35		11.9	2.27
120583	0.16		12.2	1.30
120584	0.08		7.1	
120585	0.03		1.0	
120586	0.11		2.9	
120587	0.39		4.0	
120588	0.16	0.17	2.5	
120589	0.13		3.6	
120590	0.12		2.4	
120591	0.39		3.0	
120592	0.79		4.2	
120593	0.65		5.0	
120594	1.12		5.4	
120595	0.52		7.2	
120596	0.16		3.0	
120597	0.50		4.4	
120598	0.66	0.69	3.9	
120599	0.64		3.6	
120600	<0.01		0.7	
*0218	0.89			
*CCu-1c				3.93
*BLANK	<0.01			<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3190-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment23**
Attn: **Sue Deane**

Sep-15-08

We hereby certify the following assay of 22 core samples submitted May-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120601	0.41	0.42	6.4
120602	0.42		3.8
120603	0.27		2.0
120604	0.43		3.5
120605	0.35		3.7
120606	0.36		3.1
120607	0.34		2.3
120608	0.01		0.5
120609	0.08		3.0
120610	0.18	0.20	2.4
120611	0.32		2.7
120612	0.15		2.6
120613	0.02		1.4
120614	0.02		1.5
120615	0.01		1.7
120616	0.01		1.4
120617	0.01		1.8
120618	<0.01		1.7
120619	0.01		1.0
120620	0.04	0.03	1.2
120621	0.30		3.0
120622	0.30		4.5
*0218	0.89		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3190-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment23**
Attn: **Sue Deane**

Sep-15-08

We hereby certify the following assay of 22 core samples submitted May-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
120623	0.22	0.22	3.5	
120624	0.40		4.3	
120625	1.50		>200	213.7
120626	0.26		2.3	
120627	0.24		3.0	
120628	0.11		1.8	
120647	0.59		5.3	
120648	0.26		3.6	
120649	0.07		2.2	
120650	0.01	0.01	<0.1	
120651	0.08		1.3	
120652	0.28		2.4	
120653	0.06		2.4	
120654	0.22		2.2	
120655	0.07		2.1	
120656	0.06		1.6	
120657	0.15		6.9	
120658	0.14		2.9	
120659	0.06		2.1	
120660	0.09	0.07	2.8	
120661	0.05		4.0	
120662	0.08		9.8	
*0218	0.92			
*CCu-1c				131.3
*BLANK	<0.01			<0.1

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3190-RA7

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment23**
Attn: **Sue Deane**

Sep-15-08

We hereby certify the following assay of 22 core samples submitted May-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120663	0.14	0.11	6.4
120664	0.11		6.7
120665	0.10		8.0
120666	0.66		5.0
120667	0.14		10.7
120668	0.25		4.0
120669	0.33		4.2
120670	0.16		4.0
120671	0.53		2.9
120672	0.50	0.50	3.7
120673	0.26		3.6
120674	0.35		2.1
120675	0.47		0.4
120676	0.60		2.9
120677	0.27		2.1
120678	0.42		2.2
120679	0.81		2.4
120680	0.42		2.1
120681	0.10		1.7
120682	0.25	0.27	1.8
120683	0.08		0.8
120684	0.28		1.9
*0218	0.89		
*BLANK	<0.01		

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3190RJ**

Date : Sep-15-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment23

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120513	4.3	0.94	27	42	<0.5	<5	3.70	3	16	124	420	1.89	1	0.06	<10	0.86	671	69	0.02	20	1416	15	0.18	<5	3	171	<5	0.11	<10	<10	59	<10	145	4
120514	8.7	1.18	37	43	<0.5	<5	2.31	4	21	157	832	2.92	1	0.07	<10	1.14	677	23	0.03	27	1526	28	0.44	<5	3	69	<5	0.13	<10	<10	69	<10	233	3
120515	6.7	0.84	21	57	<0.5	<5	2.09	4	16	117	729	2.22	1	0.06	<10	0.76	560	25	0.02	18	1529	25	0.30	<5	3	64	<5	0.10	<10	<10	58	<10	228	5
120516	6.1	2.12	47	106	<0.5	<5	8.86	3	27	199	503	5.09	<1	0.09	<10	2.51	2282	87	0.01	31	1502	15	0.41	<5	21	534	<5	0.05	<10	<10	138	<10	196	4
120517	3.6	1.64	50	109	<0.5	<5	4.16	3	25	182	256	3.67	<1	0.11	<10	1.70	1433	39	0.01	28	1498	11	0.41	<5	8	103	<5	0.14	<10	<10	115	<10	191	5
120518	7.5	2.35	446	59	<0.5	<5	9.72	11	31	221	288	5.65	<1	0.13	<10	2.76	3855	21	0.01	32	1561	91	0.93	<5	21	365	<5	0.03	<10	15	162	<10	268	2
120519	4.9	1.84	49	111	<0.5	<5	5.22	3	29	186	255	4.20	1	0.08	<10	2.18	1484	33	0.01	28	1519	14	0.49	<5	14	253	<5	0.12	<10	<10	132	<10	211	5
120520	3.1	1.11	45	56	<0.5	<5	4.15	4	21	105	113	3.16	<1	0.06	<10	0.78	992	17	0.01	15	1480	20	0.39	<5	5	151	<5	0.10	<10	<10	79	<10	346	8
120521	3.0	1.01	32	83	<0.5	<5	3.82	4	16	114	112	2.20	<1	0.07	<10	0.56	908	10	0.01	14	1456	25	0.08	<5	5	123	<5	0.10	<10	<10	71	<10	400	8
120522	6.4	1.17	2267	94	<0.5	<5	5.89	62	21	193	180	3.89	<1	0.14	<10	0.86	2675	19	0.01	28	1639	223	1.54	19	14	124	<5	0.05	<10	<10	134	30	2452	4
120523	11.4	1.43	218	41	<0.5	<5	9.88	6	20	193	403	4.61	<1	0.06	<10	1.08	4166	12	0.01	26	986	1055	1.49	<5	17	333	<5	<0.01	<10	15	126	<10	311	1
120524	3.6	1.83	54	100	<0.5	<5	10.53	2	25	251	264	5.08	<1	0.10	<10	1.23	2949	10	0.01	28	1497	18	0.30	<5	24	260	<5	0.02	<10	<10	174	<10	241	3
120525	0.5	1.09	6579	23	<0.5	19	6.60	129	194	16	76	4.09	<1	0.05	12	0.25	795	13	0.08	36	1330	15	1.54	<5	2	102	<5	0.06	<10	<10	43	<10	94	10
120526	2.3	1.72	35	145	<0.5	<5	9.56	2	25	209	110	4.84	<1	0.08	<10	1.42	2612	8	0.01	25	1518	13	0.33	<5	18	313	<5	0.07	<10	<10	136	<10	266	7
120527	2.9	2.39	38	358	<0.5	<5	12.96	2	26	229	211	5.27	<1	0.05	<10	2.17	3394	8	0.01	32	1354	42	0.24	<5	23	439	<5	<0.01	<10	10	178	<10	251	2
120528	3.0	1.91	60	372	<0.5	<5	13.28	3	26	230	140	5.19	<1	0.09	<10	1.30	3650	33	0.01	30	1385	11	0.49	<5	19	273	<5	0.01	<10	13	163	<10	284	2
120529	3.8	2.01	35	57	<0.5	<5	14.22	2	25	224	249	5.42	<1	0.07	<10	1.47	3435	18	0.01	30	1384	11	0.36	<5	22	298	<5	0.02	<10	12	168	<10	266	3
120530	3.7	1.83	13	140	<0.5	<5	4.73	3	28	162	405	4.51	<1	0.10	<10	1.98	1465	21	0.02	26	1512	26	0.38	<5	9	170	<5	0.15	<10	<10	143	<10	224	4
120531	4.1	2.33	23	50	<0.5	<5	6.41	4	34	210	414	5.58	<1	0.08	<10	2.53	1949	28	0.02	30	1694	60	0.68	<5	15	288	<5	0.12	<10	<10	174	<10	341	4
120532	3.5	2.08	89	40	<0.5	<5	11.27	7	30	232	300	5.90	<1	0.06	<10	1.74	2940	46	0.01	31	1462	38	1.27	<5	20	200	<5	0.11	<10	<10	179	<10	605	3
120533	2.7	2.36	34	42	<0.5	<5	9.89	3	34	294	237	6.11	1	0.06	<10	1.97	2691	27	0.01	37	1616	14	0.58	<5	28	173	<5	0.12	<10	<10	225	<10	338	4
120534	2.0	2.00	10	46	<0.5	<5	6.73	2	31	245	320	5.14	<1	0.07	<10	1.81	1810	25	0.02	31	1735	14	0.38	<5	16	116	<5	0.15	<10	<10	185	<10	247	5
120535	1.0	1.83	14	45	0.7	<5	4.98	3	27	177	352	4.70	<1	0.11	<10	1.70	1826	23	0.02	30	1460	26	0.39	<5	10	83	<5	0.15	<10	<10	159	<10	248	5
120536	1.0	1.86	31	44	0.7	<5	7.56	6	27	208	288	5.44	<1	0.08	<10	1.64	2668	65	0.02	29	1344	93	1.30	<5	15	126	<5	0.13	<10	<10	158	<10	513	7
120537	0.5	0.83	9	19	<0.5	<5	2.08	3	12	95	369	2.37	1	0.02	<10	0.79	938	46	0.01	14	774	32	0.53	<5	5	45	<5	0.06	<10	<10	66	<10	210	3
120538	1.2	2.38	34	34	0.8	<5	5.17	10	26	216	370	7.18	1	0.06	<10	2.26	2969	128	0.01	30	1375	251	2.59	<5	15	98	<5	0.13	<10	<10	169	<10	843	7
120539	2.1	1.41	28	54	0.5	<5	4.87	5	20	183	307	3.50	<1	0.07	<10	1.23	1741	79	0.02	26	1463	52	0.38	<5	8	119	<5	0.11	<10	<10	121	<10	390	8
120540	1.3	1.09	24	33	<0.5	<5	6.13	19	20	149	218	3.35	1	0.05	<10	1.01	1678	101	0.01	21	953	805	0.89	<5	9	117	<5	0.06	<10	<10	95	<10	1942	6
120541	0.8	1.77	48	40	<0.5	<5	7.02	28	21	197	156	5.66	1	0.05	<10	1.55	2724	83	0.01	25	1255	344	2.25	5	14	110	<5	0.09	<10	<10	149	<10	3153	8
120542	1.7	1.33	17	56	0.5	<5	2.56	3	20	158	404	3.17	<1	0.12	<10	1.23	1013	84	0.02	24	1448	32	0.23	<5	5	73	<5	0.13	<10	<10	103	<10	210	5

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3190RJ**

Date : Sep-15-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment23

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120543	3.2	1.21	17	34	<0.5	<5	1.47	2	19	116	471	2.70	<1	0.07	<10	1.23	742	117	0.02	22	1410	9	0.17	<5	3	55	<5	0.11	<10	<10	75	<10	190	5
120544	1.3	1.09	53	29	<0.5	<5	4.52	3	18	98	142	3.00	<1	0.05	<10	0.84	1329	42	0.01	14	1151	37	0.62	<5	3	108	<5	0.07	<10	<10	62	<10	256	7
120545	1.7	0.73	17	28	<0.5	<5	2.73	4	12	84	206	1.57	<1	0.06	<10	0.34	465	52	0.02	9	1401	12	0.10	<5	3	117	<5	0.10	<10	<10	53	<10	310	10
120546	2.1	1.10	12	68	<0.5	<5	2.08	12	15	106	268	2.17	<1	0.10	<10	0.96	732	51	0.03	16	1382	419	0.20	<5	3	62	<5	0.11	<10	<10	70	<10	1430	7
120547	2.2	1.28	18	46	<0.5	<5	1.73	2	20	127	401	2.76	<1	0.07	<10	1.24	621	188	0.03	23	1424	7	0.20	<5	2	75	<5	0.13	<10	<10	76	<10	184	5
120548	2.3	0.93	14	73	<0.5	<5	1.73	2	13	88	434	1.62	<1	0.13	<10	0.86	537	50	0.03	15	1415	11	0.07	<5	2	66	<5	0.12	<10	<10	50	<10	127	8
120549	0.8	1.34	14	54	<0.5	<5	4.53	2	15	127	209	2.59	<1	0.07	<10	1.34	1558	32	0.02	19	1409	44	0.05	<5	5	117	<5	0.11	<10	<10	80	24	131	9
120550	<0.2	1.01	<5	237	0.7	<5	0.52	1	7	112	2	2.10	<1	0.51	<10	0.62	571	2	0.07	7	693	2	<0.01	<5	2	62	5	0.14	<10	<10	41	<10	54	3
120551	2.3	1.47	17	44	<0.5	<5	6.79	3	19	171	207	3.23	<1	0.08	<10	1.29	2215	26	0.02	25	1446	310	0.12	<5	10	125	<5	0.11	<10	<10	115	<10	255	9
120552	0.3	2.24	18	26	<0.5	<5	10.43	2	19	219	153	4.74	<1	0.03	<10	1.96	3361	23	0.01	30	1239	17	0.08	<5	15	201	<5	0.09	<10	<10	158	34	116	6
120553	0.2	1.52	14	41	<0.5	<5	4.80	2	15	121	143	3.24	<1	0.09	<10	1.36	2064	43	0.02	19	1263	9	0.09	<5	10	108	<5	0.10	<10	<10	97	<10	118	7
120554	<0.2	1.29	14	41	<0.5	<5	3.25	3	15	99	91	2.73	<1	0.07	<10	1.09	1265	58	0.02	17	1417	14	0.04	<5	4	102	<5	0.09	<10	<10	64	<10	234	8
120555	0.3	1.28	22	32	<0.5	<5	4.37	3	19	109	112	3.21	1	0.05	<10	0.93	1208	52	0.01	17	1280	26	0.08	<5	5	130	<5	0.09	<10	<10	78	<10	235	8
120556	1.2	1.40	28	48	0.5	<5	4.47	3	20	168	212	3.39	<1	0.08	<10	1.18	1850	52	0.02	23	1417	27	0.23	<5	9	120	<5	0.09	<10	<10	114	<10	231	6
120557	5.3	2.06	65	48	<0.5	<5	8.74	7	26	163	200	5.63	1	0.07	<10	1.58	3264	37	0.01	23	1241	1077	1.55	<5	12	184	<5	0.05	<10	13	126	<10	657	4
120558	2.0	2.29	67	47	<0.5	<5	10.46	3	24	199	149	5.39	<1	0.05	<10	1.76	4034	51	0.01	27	1306	61	0.58	<5	15	195	<5	0.07	<10	15	156	<10	261	3
120559	1.9	1.80	27	49	<0.5	<5	6.90	13	22	177	237	3.83	<1	0.08	<10	1.64	2458	39	0.01	24	1258	102	0.34	<5	10	142	<5	0.08	<10	<10	126	16	1210	3
120560	1.1	2.17	18	46	<0.5	<5	5.47	3	25	193	156	4.28	<1	0.05	<10	2.46	1731	18	0.02	27	1282	45	0.20	<5	8	108	<5	0.12	<10	<10	132	<10	320	2
120561	1.8	2.31	31	47	<0.5	<5	6.05	18	27	222	165	5.16	<1	0.07	<10	2.42	2748	19	0.01	31	1440	263	0.57	<5	17	153	<5	0.08	<10	<10	170	19	1697	2
120562	2.5	2.00	31	66	<0.5	<5	7.79	7	26	223	160	5.05	<1	0.10	<10	2.31	2629	19	0.02	32	1371	359	0.49	<5	22	304	<5	0.04	<10	<10	171	<10	751	3
120563	3.7	2.12	69	61	<0.5	<5	7.96	20	32	162	342	6.18	<1	0.07	<10	1.67	2885	26	0.01	28	1196	265	1.63	<5	10	187	<5	0.07	<10	12	131	22	1848	4
120564	3.7	1.46	28	61	<0.5	<5	6.94	2	24	179	310	3.55	<1	0.09	<10	1.24	2179	33	0.02	28	1411	17	0.14	<5	13	166	<5	0.07	<10	<10	131	<10	179	5
120565	3.3	1.73	37	51	<0.5	<5	8.10	14	25	191	255	4.26	<1	0.09	<10	1.47	2795	31	0.01	29	1320	163	0.65	<5	14	173	<5	0.06	<10	<10	145	15	1324	4
120566	3.3	3.48	317	23	<0.5	10	3.52	8	26	216	74	14.47	<1	0.02	<10	3.18	3426	39	<0.01	25	1275	212	>5.00	<5	17	64	<5	0.02	<10	28	183	<10	414	6
120567	3.6	2.70	132	68	<0.5	5	5.33	13	32	264	162	9.92	<1	0.08	<10	2.38	3037	13	0.01	30	1429	841	>5.00	<5	20	97	<5	0.04	<10	14	198	16	1151	4
120568	<0.2	1.21	<5	187	<0.5	<5	2.41	<1	11	36	6	2.56	<1	0.24	10	0.78	560	<2	0.04	3	952	30	0.18	<5	3	55	<5	0.10	<10	<10	39	<10	81	5
120569	3.2	1.76	30	88	<0.5	<5	10.24	2	29	252	335	4.99	<1	0.10	<10	1.14	2817	35	0.02	32	1388	49	0.36	<5	18	184	<5	0.10	<10	<10	182	<10	288	6
120570	2.5	1.44	33	64	<0.5	<5	13.43	11	18	132	127	5.14	<1	0.07	<10	1.34	3405	56	0.01	19	942	134	0.75	<5	12	447	<5	0.03	<10	14	95	14	1082	3
120571	3.8	2.04	52	44	<0.5	<5	8.00	7	26	200	428	5.66	<1	0.07	<10	1.75	2697	84	0.01	28	1246	190	1.34	<5	15	181	<5	<0.01	<10	<10	145	<10	624	2
120572	4.0	2.47	108	66	<0.5	8	5.00	55	23	215	188	9.39	<1	0.04	<10	2.21	2773	54	0.01	26	1166	496	>5.00	<5	17	95	<5	0.01	<10	15	163	55	5152	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3190RJ**

Date : Sep-15-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment23

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120573	3.5	2.09	45	47	<0.5	<5	8.66	3	30	263	313	5.34	<1	0.09	<10	1.62	2807	41	0.01	34	1529	39	0.96	<5	21	171	<5	0.10	<10	<10	199	<10	291	3
120574	3.8	2.18	50	39	<0.5	<5	9.71	59	26	233	232	6.54	<1	0.06	<10	1.65	2884	35	0.01	27	1259	252	2.52	<5	21	163	<5	0.08	<10	<10	178	61	5492	3
120575	180.3	0.85	198	219	<0.5	92	5.43	6	17	24	3705	3.64	4	0.17	<10	0.20	667	67	0.03	35	599	242	1.41	221	2	187	<5	0.06	<10	<10	22	19	265	9
120576	2.8	1.34	51	32	<0.5	<5	>15.00	6	25	171	176	4.23	<1	0.09	<10	0.69	3266	36	<0.01	24	921	29	1.01	<5	16	216	<5	0.04	<10	10	126	<10	455	2
120577	5.1	2.23	43	29	<0.5	<5	10.57	19	27	239	375	6.24	<1	0.04	<10	1.71	2707	47	0.01	30	1253	130	1.66	<5	21	198	<5	0.09	<10	<10	180	19	1727	3
120578	11.4	1.97	178	35	<0.5	13	6.95	194	28	177	928	9.58	<1	0.05	<10	1.51	2963	66	0.01	23	1031	1144	>5.00	<5	15	127	<5	0.02	<10	18	134	201	>10000	4
120579	6.0	2.64	188	24	<0.5	11	1.74	62	24	194	110	12.72	<1	0.02	<10	2.24	2746	39	<0.01	22	1049	1093	>5.00	<5	15	30	<5	0.04	<10	23	136	61	5935	5
120580	4.9	2.18	192	32	<0.5	12	2.74	109	30	168	211	12.35	<1	0.04	<10	1.91	2506	24	<0.01	20	914	751	>5.00	<5	12	47	<5	0.02	<10	23	117	119	>10000	4
120581	11.1	2.20	51	53	<0.5	10	8.63	107	30	235	612	6.92	1	0.07	<10	1.77	3041	62	<0.01	30	1331	2107	3.49	<5	21	210	<5	0.02	<10	14	169	115	>10000	2
120582	11.9	2.20	56	79	<0.5	7	8.87	208	26	165	473	7.94	1	0.08	<10	1.61	2893	110	<0.01	23	864	3950	4.99	<5	13	187	<5	0.01	<10	16	123	225	>10000	3
120583	12.2	1.92	70	39	<0.5	6	10.91	114	28	165	251	5.90	1	0.13	<10	1.17	2956	126	<0.01	23	1084	4718	2.86	<5	13	190	<5	<0.01	<10	14	120	128	>10000	1
120584	7.1	1.83	42	63	<0.5	<5	9.64	49	22	199	205	5.10	<1	0.18	<10	1.03	2590	85	0.01	27	1164	2412	1.63	<5	14	174	<5	0.05	<10	10	134	53	4944	2
120585	1.0	1.22	5	47	<0.5	<5	2.29	1	28	53	105	2.47	<1	0.18	<10	0.83	540	6	0.03	6	688	130	0.59	<5	3	38	<5	0.13	<10	<10	38	<10	171	6
120586	2.9	1.90	70	72	<0.5	<5	8.96	6	27	179	199	6.11	<1	0.19	<10	0.97	3294	37	0.01	25	1004	121	1.19	<5	14	130	<5	0.07	<10	15	123	<10	591	3
120587	4.0	2.27	49	56	<0.5	<5	9.58	16	26	179	293	6.37	<1	0.14	<10	1.44	2959	33	<0.01	27	1223	560	1.76	<5	17	174	<5	0.03	<10	13	139	17	1661	2
120588	2.5	2.57	35	44	<0.5	<5	11.48	3	29	229	204	6.23	<1	0.09	<10	2.05	3515	13	<0.01	32	1318	43	0.36	<5	23	268	<5	<0.01	<10	14	174	<10	375	2
120589	3.6	2.02	28	67	<0.5	<5	10.74	20	25	179	209	5.00	<1	0.07	<10	1.95	2929	45	<0.01	25	1165	653	1.02	<5	16	259	<5	0.04	<10	11	131	24	2026	3
120590	2.4	2.13	45	83	<0.5	<5	11.78	3	28	221	162	5.66	<1	0.07	<10	1.67	3565	15	<0.01	33	1235	23	0.63	<5	21	326	<5	<0.01	<10	14	170	<10	327	1
120591	3.0	1.79	22	43	<0.5	<5	12.58	3	24	175	242	4.73	<1	0.03	<10	1.35	3175	29	<0.01	24	1007	79	0.28	<5	15	241	<5	0.04	<10	12	131	<10	478	3
120592	4.2	1.61	27	182	<0.5	<5	6.33	2	24	206	332	4.57	<1	0.09	<10	1.13	2906	118	0.01	26	1445	11	0.17	<5	17	174	<5	0.09	<10	<10	150	<10	408	5
120593	5.0	1.49	238	37	<0.5	<5	8.60	9	27	147	211	5.38	<1	0.06	<10	0.72	3059	144	<0.01	33	826	46	1.75	<5	13	160	<5	0.02	<10	13	122	<10	539	2
120594	5.4	1.85	176	123	<0.5	<5	8.09	6	22	165	421	5.25	<1	0.11	<10	1.17	3608	29	<0.01	21	1086	70	0.70	<5	16	170	<5	0.05	<10	14	141	<10	411	3
120595	7.2	1.89	47	70	<0.5	<5	10.07	4	28	217	500	5.35	<1	0.07	<10	1.29	3163	30	<0.01	30	1371	101	0.51	<5	21	244	<5	0.04	<10	11	161	<10	682	4
120596	3.0	1.16	50	31	<0.5	<5	>15.00	2	13	88	143	3.15	<1	0.04	<10	1.01	4251	25	<0.01	14	606	53	0.50	<5	10	390	<5	0.01	<10	17	73	<10	144	1
120597	4.4	0.47	57	50	<0.5	<5	7.78	3	24	79	277	4.22	<1	0.17	<10	1.03	2905	29	<0.01	25	1066	22	0.31	<5	17	235	<5	<0.01	<10	13	51	<10	339	1
120598	3.9	1.70	19	95	<0.5	<5	8.11	1	20	176	217	4.24	<1	0.08	<10	1.43	2726	102	<0.01	22	1196	6	0.09	<5	16	197	<5	0.05	<10	<10	133	<10	232	4
120599	3.6	2.02	92	41	<0.5	<5	9.50	3	25	213	180	5.33	1	0.07	<10	1.16	3554	109	<0.01	26	1101	38	0.25	<5	20	188	<5	0.01	<10	14	161	<10	345	2
120600	0.7	1.07	<5	257	<0.5	<5	0.85	<1	10	117	7	2.31	<1	0.52	10	0.66	709	4	0.06	7	722	8	<0.01	<5	3	64	5	0.13	<10	<10	46	<10	73	2
120601	6.4	1.49	81	28	<0.5	5	7.72	28	22	176	419	4.66	<1	0.06	<10	1.00	2601	37	<0.01	25	1071	390	1.69	<5	15	174	<5	<0.01	<10	10	129	27	2690	1
120602	3.8	0.59	45	92	<0.5	<5	6.50	2	29	82	470	5.43	<1	0.15	<10	1.20	2470	36	<0.01	29	1289	25	0.45	<5	19	226	<5	<0.01	<10	12	67	<10	264	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3190RJ**

Date : Sep-15-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment23

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120603	2.0	1.58	16	49	<0.5	<5	6.73	2	25	200	214	4.38	<1	0.07	<10	1.33	2169	30	<0.01	29	1328	11	0.23	<5	16	194	<5	0.04	<10	<10	144	<10	284	2
120604	3.5	1.74	22	162	<0.5	<5	6.82	2	24	156	299	5.31	<1	0.07	<10	1.12	2603	31	0.01	24	1075	15	0.61	<5	15	222	<5	0.05	<10	11	127	<10	225	3
120605	3.7	1.42	79	36	<0.5	<5	7.25	4	21	143	196	5.36	<1	0.06	<10	1.12	2529	56	<0.01	19	839	51	3.16	<5	13	197	<5	0.01	<10	12	113	<10	358	2
120606	3.1	1.79	45	37	<0.5	<5	7.74	2	24	197	196	4.84	<1	0.05	<10	1.36	2706	15	<0.01	26	1151	19	1.02	<5	16	186	<5	0.01	<10	10	145	<10	172	2
120607	2.3	1.37	65	75	<0.5	<5	6.78	2	25	189	135	4.09	<1	0.17	<10	0.85	1935	22	0.01	26	1112	29	1.20	<5	15	102	<5	0.05	<10	<10	138	<10	155	2
120608	0.5	0.81	5	341	<0.5	<5	2.67	1	11	46	55	2.02	<1	0.17	14	0.61	621	2	0.02	6	664	92	0.26	<5	3	88	<5	<0.01	<10	<10	29	<10	92	5
120609	3.0	1.41	80	85	<0.5	<5	7.94	29	19	192	146	4.18	<1	0.12	<10	1.07	2324	8	<0.01	24	1092	356	1.30	<5	17	218	<5	0.01	<10	<10	136	16	1690	1
120610	2.4	1.55	33	64	<0.5	<5	5.71	2	23	185	169	3.90	1	0.09	<10	1.35	1922	23	<0.01	27	1132	29	0.71	<5	16	155	<5	0.04	<10	<10	144	<10	223	1
120611	2.7	1.63	141	43	<0.5	<5	5.85	5	19	150	138	4.41	<1	0.07	<10	1.43	2169	15	<0.01	19	933	162	1.32	<5	15	134	<5	0.03	<10	<10	123	<10	288	2
120612	2.6	1.78	198	109	<0.5	<5	5.80	8	20	150	148	4.56	<1	0.10	<10	1.47	2314	24	<0.01	21	1001	254	1.08	<5	11	143	<5	<0.01	<10	10	102	<10	518	1
120613	1.4	2.15	77	36	<0.5	<5	9.46	3	26	189	87	4.73	<1	0.07	<10	1.75	2111	2	<0.01	29	1119	24	0.66	<5	14	259	<5	0.01	<10	<10	139	<10	118	2
120614	1.5	1.97	48	40	<0.5	<5	10.49	2	24	198	74	4.45	1	0.07	<10	1.58	2502	6	<0.01	28	1195	28	0.48	<5	17	297	<5	0.02	<10	<10	144	<10	98	2
120615	1.7	2.12	49	36	<0.5	<5	9.49	1	29	223	137	5.23	<1	0.06	<10	1.61	2430	<2	<0.01	33	1284	20	0.89	<5	20	202	<5	0.04	<10	<10	171	<10	81	2
120616	1.4	1.87	91	42	<0.5	<5	8.10	2	30	217	78	4.56	<1	0.11	<10	1.42	1851	<2	<0.01	32	1380	23	0.84	<5	16	176	<5	0.02	<10	<10	145	<10	69	2
120617	1.8	1.97	50	166	<0.5	<5	8.46	1	27	163	87	4.88	<1	0.19	<10	1.86	1914	<2	<0.01	29	1354	21	0.83	<5	14	214	<5	<0.01	<10	<10	114	<10	64	1
120618	1.7	1.84	41	48	<0.5	<5	9.32	1	25	172	108	4.10	<1	0.10	<10	1.57	1886	<2	<0.01	28	1122	24	0.51	<5	14	177	<5	0.01	<10	<10	107	<10	67	1
120619	1.0	1.99	42	43	<0.5	<5	8.90	1	24	160	49	4.20	<1	0.20	<10	1.62	1891	<2	<0.01	28	1153	17	0.48	<5	12	200	<5	0.02	<10	<10	94	<10	69	2
120620	1.2	2.01	36	64	<0.5	<5	8.29	1	24	167	64	4.72	<1	0.11	<10	1.55	2213	<2	<0.01	26	1106	27	0.74	<5	12	154	<5	0.01	<10	10	104	<10	86	1
120621	3.0	1.48	98	85	<0.5	<5	3.39	9	18	63	131	4.66	<1	0.26	<10	0.88	1621	16	<0.01	9	1060	259	1.48	<5	5	81	<5	<0.01	<10	<10	56	10	1087	1
120622	4.5	0.84	141	41	<0.5	<5	5.83	32	7	46	99	3.32	<1	0.10	<10	0.53	2358	5	<0.01	2	504	1767	1.80	<5	2	286	<5	<0.01	<10	11	29	39	4143	1
120623	3.5	1.64	211	84	<0.5	<5	4.00	14	16	24	187	5.10	<1	0.17	<10	1.11	2372	13	<0.01	3	1125	257	1.78	<5	4	152	<5	0.01	<10	<10	78	14	1468	2
120624	4.3	0.84	346	50	<0.5	<5	8.00	46	8	31	155	4.28	<1	0.10	<10	0.60	2771	14	<0.01	2	537	592	3.48	<5	2	206	<5	<0.01	<10	11	35	53	5377	1
120625	>200.0	0.77	1849	103	<0.5	61	4.57	38	69	26	2325	3.11	1	0.08	<10	0.25	885	125	0.05	26	860	437	0.73	368	2	141	<5	0.03	<10	<10	20	19	368	6
120626	2.3	0.90	248	97	<0.5	<5	4.56	7	10	47	84	3.88	<1	0.16	<10	0.52	2238	15	<0.01	3	822	297	1.77	<5	3	92	<5	<0.01	<10	<10	45	<10	329	1
120627	3.0	1.19	135	131	<0.5	<5	3.55	14	12	52	157	4.62	<1	0.21	<10	0.65	2035	50	0.01	3	1071	286	1.69	<5	3	61	<5	<0.01	<10	<10	50	16	1870	1
120628	1.8	1.50	70	94	<0.5	<5	5.72	2	16	18	122	4.82	<1	0.19	<10	0.95	2291	9	0.01	3	1244	18	1.02	<5	3	156	<5	0.01	<10	<10	71	<10	217	1
120647	5.3	0.87	20	62	<0.5	<5	2.00	2	18	131	598	2.50	<1	0.09	<10	0.92	664	47	0.02	21	1606	17	0.24	<5	3	56	<5	0.09	<10	<10	62	<10	210	5
120648	3.6	2.44	33	50	<0.5	<5	9.13	2	37	253	406	5.97	<1	0.04	<10	3.24	2158	39	0.01	35	1503	13	0.43	<5	24	393	<5	0.11	<10	<10	209	<10	381	4
120649	2.2	1.27	28	63	<0.5	<5	2.95	2	26	154	232	3.56	<1	0.07	<10	1.22	781	97	0.02	25	1584	12	0.31	<5	4	87	<5	0.11	<10	<10	92	<10	254	4
120650	<0.2	0.95	<5	287	<0.5	<5	0.61	<1	10	114	4	2.38	<1	0.49	<10	0.66	669	<2	0.06	7	883	5	<0.01	<5	3	45	<5	0.13	<10	<10	44	<10	72	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3190RJ**

Date : Sep-15-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment23

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120651	1.3	0.82	33	50	<0.5	<5	3.02	3	21	119	125	2.49	<1	0.05	<10	0.53	647	61	0.01	19	1480	8	0.17	<5	3	127	<5	0.08	<10	<10	58	<10	310	6
120652	2.4	1.12	20	66	<0.5	<5	4.47	1	18	116	272	2.80	<1	0.09	<10	1.08	1048	57	0.02	19	1597	11	0.17	<5	4	77	<5	0.09	<10	<10	66	<10	161	5
120653	2.4	2.06	25	130	<0.5	<5	4.41	1	32	200	322	5.36	<1	0.06	11	2.18	1370	24	0.02	32	2029	11	0.39	<5	12	150	<5	0.11	<10	<10	145	<10	210	5
120654	2.2	1.27	36	51	<0.5	<5	6.31	2	20	158	232	3.54	<1	0.06	<10	1.04	952	22	0.01	27	1605	15	0.55	<5	3	166	<5	0.08	<10	<10	70	<10	242	4
120655	2.1	2.04	56	74	<0.5	<5	11.02	1	32	219	236	5.38	<1	0.08	<10	2.35	2553	55	0.01	33	1503	34	0.36	<5	26	781	<5	0.01	<10	<10	151	<10	129	2
120656	1.6	1.62	21	47	<0.5	<5	5.49	1	27	175	219	4.19	<1	0.06	<10	1.49	1291	33	0.02	28	1543	9	0.23	<5	5	107	<5	0.13	<10	<10	124	<10	194	3
120657	6.9	1.51	173	33	<0.5	<5	11.39	26	24	157	473	3.94	<1	0.06	<10	1.59	3478	36	0.01	23	1152	1831	1.12	<5	9	202	<5	0.08	<10	11	114	23	2492	2
120658	2.9	1.42	22	59	<0.5	<5	1.58	2	29	156	476	3.87	<1	0.08	<10	1.31	711	58	0.02	29	1641	28	0.49	<5	3	58	<5	0.15	<10	<10	104	<10	211	2
120659	2.1	1.21	32	62	<0.5	<5	4.45	2	17	119	131	2.77	<1	0.11	<10	1.28	1357	27	0.02	19	1395	13	0.19	<5	7	109	<5	0.07	<10	<10	78	<10	164	5
120660	2.8	1.44	56	51	<0.5	<5	5.10	3	21	135	126	3.52	<1	0.09	<10	1.40	1747	43	0.02	20	1505	222	0.44	<5	8	121	<5	0.06	<10	<10	90	<10	265	5
120661	4.0	1.90	308	37	<0.5	<5	10.71	7	26	203	203	4.73	<1	0.07	<10	2.01	3076	12	<0.01	28	1149	25	1.04	<5	17	250	<5	0.02	<10	<10	144	<10	174	2
120662	9.8	1.91	110	75	<0.5	<5	8.32	25	31	194	298	5.95	<1	0.15	<10	2.11	2783	27	0.01	33	1447	462	1.15	<5	22	282	<5	0.01	<10	10	136	28	2852	2
120663	6.4	2.32	72	32	<0.5	<5	10.51	3	24	195	262	5.92	<1	0.06	<10	2.12	3366	10	<0.01	26	1254	21	1.35	<5	17	288	<5	0.01	<10	14	145	<10	332	2
120664	6.7	2.16	76	30	<0.5	<5	6.77	4	26	208	257	4.79	<1	0.09	<10	2.10	2723	14	0.01	27	1287	97	1.14	<5	13	126	<5	0.06	<10	<10	124	<10	293	3
120665	8.0	1.23	45	51	<0.5	<5	5.50	3	25	147	377	3.03	<1	0.05	<10	1.20	1453	22	0.01	24	1365	18	0.55	<5	4	145	<5	0.09	<10	<10	82	<10	230	5
120666	5.0	1.43	32	57	<0.5	<5	6.01	6	24	177	396	3.92	<1	0.07	<10	1.30	2508	13	0.01	25	1375	308	0.70	<5	10	113	<5	0.08	<10	<10	118	11	680	5
120667	10.7	1.27	53	28	<0.5	<5	8.97	99	24	138	675	4.46	1	0.04	<10	1.21	2324	7	0.01	20	1138	1040	2.59	<5	7	119	<5	0.04	<10	<10	89	88	8491	3
120668	4.0	0.87	10	77	<0.5	<5	2.23	2	13	82	524	1.89	<1	0.07	<10	0.91	760	19	0.02	13	1378	12	0.07	<5	3	59	<5	0.09	<10	<10	48	<10	210	6
120669	4.2	0.86	16	92	<0.5	<5	4.99	3	20	158	425	1.97	<1	0.09	<10	0.83	1105	25	0.02	19	1534	14	0.11	<5	8	72	<5	0.09	<10	<10	76	<10	284	6
120670	4.0	1.12	30	118	<0.5	<5	7.21	4	21	109	398	4.77	<1	0.12	<10	1.98	2488	64	0.02	20	1276	33	0.27	<5	17	419	<5	0.05	<10	<10	91	<10	324	3
120671	2.9	1.07	15	111	<0.5	<5	4.82	6	18	128	292	3.37	<1	0.05	<10	0.94	1213	23	0.01	14	1256	13	0.08	<5	8	113	<5	0.07	<10	<10	91	<10	444	7
120672	3.7	1.69	46	46	<0.5	<5	8.94	2	24	168	228	4.67	<1	0.06	<10	1.53	2829	91	0.01	25	1166	20	0.42	<5	15	227	<5	0.04	<10	<10	131	<10	309	4
120673	3.6	1.50	73	27	<0.5	<5	10.08	4	25	184	209	4.17	<1	0.05	<10	1.26	2947	90	0.01	23	1211	67	0.74	<5	14	154	<5	0.05	<10	<10	117	<10	507	5
120674	2.1	0.89	16	57	<0.5	<5	2.49	2	16	95	308	2.16	<1	0.08	<10	0.88	971	134	0.02	16	1286	81	0.12	<5	3	58	<5	0.09	<10	<10	52	<10	288	6
120675	0.4	1.20	5550	56	<0.5	14	6.80	112	181	58	81	4.06	<1	0.10	12	0.32	874	13	0.10	33	1190	21	1.32	5	2	104	<5	0.07	<10	<10	49	<10	118	10
120676	2.9	0.96	37	52	<0.5	<5	2.84	2	19	123	508	2.67	<1	0.07	<10	0.95	824	119	0.03	19	1218	19	0.38	<5	3	72	<5	0.09	<10	<10	65	<10	160	4
120677	2.1	0.77	53	37	<0.5	<5	2.05	3	17	105	292	2.06	<1	0.05	<10	0.78	531	66	0.02	17	1244	23	0.29	<5	2	63	<5	0.08	<10	<10	47	<10	158	4
120678	2.2	1.18	20	48	<0.5	<5	2.77	1	20	130	392	3.14	<1	0.07	<10	1.28	827	67	0.02	20	1304	11	0.38	<5	3	59	<5	0.10	<10	<10	84	<10	147	4
120679	2.4	1.60	21	71	<0.5	<5	7.91	2	27	213	393	4.60	<1	0.06	<10	1.36	2027	57	0.02	29	1293	35	0.42	<5	13	167	<5	0.09	<10	<10	141	<10	247	4
120680	2.1	1.43	17	27	<0.5	<5	14.19	2	25	219	285	4.43	<1	0.04	<10	0.94	2701	25	0.01	27	1161	39	0.58	<5	18	151	<5	0.07	<10	<10	173	<10	288	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120681	1.7	2.01	22	40	<0.5	<5	12.78	2	33	256	290	5.53	<1	0.06	<10	1.51	2745	17	0.02	34	1466	19	0.47	<5	21	163	<5	0.10	<10	<10	201	<10	238	3
120682	1.8	2.36	34	35	<0.5	<5	11.21	2	29	246	262	5.69	<1	0.08	<10	1.98	2895	28	0.01	31	1446	34	0.59	<5	19	191	<5	0.02	<10	<10	193	<10	260	2
120683	0.8	2.19	20	96	<0.5	<5	5.14	1	27	117	125	4.45	<1	0.07	<10	2.25	1450	13	0.02	20	1252	9	0.34	<5	9	146	<5	0.13	<10	<10	117	<10	141	6
120684	1.9	1.57	26	43	<0.5	<5	4.84	2	28	189	293	3.89	<1	0.07	<10	1.40	1420	41	0.02	27	1540	12	0.31	<5	6	122	<5	0.12	<10	<10	116	<10	237	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3190-SG1

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment23**
Attn: **Sue Deane**

Sep-15-08

We hereby certify the following geochemical analysis of 22 soils samples submitted May-09-08

Sample Name	Au ppb
4349	9
4329	21
4304	60
4282	12
4256	24
4236	3
4203	369
4176	45
4153	494
4128	135
4108	132
4071	63
4046	141
4027	237
3972	3
3932	1809
3905	48
3880	24
3851	75
3826	63
3799	27
3776	51
*0218	924
*BLANK	<1

Certified by _____

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3190-SG2

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment23**
Attn: **Sue Deane**

Sep-15-08

We *hereby certify* the following geochemical analysis of 22 soils samples submitted May-09-08

Sample Name	Au ppb
3751	57
3723	36
3702	156
3685	30
3660	27
3634	15
3612	27
3587	21
3565	30
3541	21
3523	24
3499	597
3470	51
3452	<1
3428	6
3403	90
3374	93
3356	204
3334	36
3313	157
3285	21
3253	32
*0218	900
*BLANK	<1

Certified by _____

*Quality Assaying for over 25 Years***Geochemical Analysis Certificate****8V-3190-SG3**Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment23**
Attn: **Sue Deane**

Sep-15-08

We hereby certify the following geochemical analysis of 22 soils samples submitted May-09-08

Sample Name	Au ppb
3223	75
3194	<1
3164	5
3135	<1
3117	1245
3085	440
3053	1206
3028	<1
3003	8
2981	189
2946	2
2925	143
2901	618
2871	131
2856	305
2836	332
2817	422
2803	2780
2757	540
2736	1518
2705	6
2675	15
*0218	913
*BLANK	<1

Certified by _____

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3190-SG4

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment23**
Attn: **Sue Deane**

Sep-15-08

We *hereby certify* the following geochemical analysis of 22 soils samples submitted May-09-08

Sample Name	Au ppb
2646	10
2621	11
2589	19
2565	9
2549	41
2532	7
2504	13
2470	5
2465	32
2443	33
2422	510
2396	42
2371	110
2348	28
2324	8
2303	96
2281	21
2254	119
2224	32
2196	7
2169	41
2145	11
*0218	875
*BLANK	<1

Certified by _____

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3190-SG5

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment23**
Attn: **Sue Deane**

Sep-15-08

We *hereby certify* the following geochemical analysis of 22 soils samples submitted May-09-08

Sample Name	Au ppb
2127	<1
2114	3
2112	6
2109	27
2107	28
2102	15
2090	23
2075	12
2042	12
2013	9
1979	20
1949	3
1920	<1
1882	10
1859	4
1829	68
1782	16
*0218	891
*BLANK	<1

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3190SJ

Date : Sep-15-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment23

Sample type: soils

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
4349	<0.2	1.95	11	144	<0.5	<5	0.34	<1	22	22	41	4.87	<1	0.05	14	0.85	1152	<2	0.01	28	1254	21	<0.01	<5	6	20	<5	0.10	<10	<10	61	<10	127	2
4329	<0.2	2.35	10	90	<0.5	<5	0.16	<1	15	24	28	4.66	<1	0.04	13	0.72	550	<2	0.01	20	1244	27	0.02	<5	3	14	<5	0.08	<10	<10	65	<10	104	2
4304	1.9	2.30	102	103	<0.5	<5	0.19	2	25	17	33	5.86	<1	0.05	22	0.62	1400	5	0.01	17	1585	29	0.04	<5	4	11	<5	0.10	<10	<10	54	<10	120	6
4282	0.3	2.01	10	175	<0.5	<5	0.39	<1	19	21	25	4.60	<1	0.04	15	0.81	1153	<2	0.01	25	1371	17	0.03	<5	4	22	<5	0.07	<10	<10	57	<10	126	2
4256	1.3	1.75	38	53	<0.5	<5	0.04	1	6	8	8	2.60	<1	0.05	39	0.21	176	5	0.03	2	583	65	0.10	<5	1	<1	<5	0.13	<10	<10	61	<10	52	44
4236	0.4	1.89	9	96	<0.5	<5	0.24	<1	17	21	27	4.67	<1	0.05	13	0.73	781	<2	0.01	21	1153	20	0.02	<5	3	16	<5	0.10	<10	<10	60	<10	104	2
4203	11.9	0.72	62	50	<0.5	<5	0.05	1	3	4	50	2.53	<1	0.06	11	0.05	82	<2	0.02	3	1309	93	0.09	<5	<1	9	<5	0.01	<10	<10	30	<10	47	1
4176	2.2	0.56	51	49	<0.5	<5	<0.01	1	2	3	23	2.13	<1	0.06	12	0.03	36	<2	0.01	1	931	35	0.06	<5	<1	4	<5	0.01	<10	<10	36	<10	27	1
4153	6.9	2.47	214	106	<0.5	<5	0.14	4	51	18	99	6.96	<1	0.07	20	0.78	2806	<2	0.02	23	2034	71	0.04	<5	5	8	<5	0.06	<10	<10	49	<10	185	4
4128	1.2	1.82	39	61	<0.5	<5	0.11	<1	23	17	43	5.75	<1	0.06	11	0.82	1278	<2	0.01	17	1167	34	0.03	<5	4	8	<5	0.10	<10	<10	53	<10	121	4
4108	1.9	1.21	23	59	<0.5	<5	0.01	<1	4	5	5	1.09	<1	0.05	10	0.05	123	2	0.01	1	461	62	0.03	<5	1	3	<5	0.08	<10	<10	42	<10	15	1
4071	4.0	0.93	33	47	<0.5	<5	0.03	1	4	4	14	2.01	<1	0.07	16	0.12	262	2	0.02	3	1258	42	0.05	<5	<1	3	<5	0.01	<10	<10	27	<10	35	1
4046	2.3	0.77	67	35	<0.5	<5	<0.01	1	3	5	13	4.37	<1	0.05	<10	0.04	34	4	0.02	<1	800	47	0.07	<5	1	4	<5	0.03	<10	<10	46	<10	28	2
4027	9.7	2.95	145	87	<0.5	<5	0.08	4	68	14	51	8.13	<1	0.05	77	0.48	2692	5	0.01	10	2147	179	0.11	<5	3	3	<5	0.05	<10	11	43	<10	357	5
3972	0.6	2.02	17	56	<0.5	<5	0.06	<1	14	11	14	5.17	<1	0.05	11	0.77	854	<2	0.01	5	1358	16	0.03	<5	1	3	<5	0.03	<10	<10	50	<10	110	2
3932	5.5	1.71	689	57	<0.5	6	<0.01	12	5	13	42	11.69	<1	0.05	12	0.17	396	<2	0.01	<1	1805	72	0.12	<5	1	9	<5	0.04	<10	13	47	<10	74	4
3905	11.4	0.94	35	45	<0.5	<5	0.07	1	21	7	16	3.37	<1	0.06	13	0.09	959	3	0.02	3	1087	58	0.08	<5	<1	7	<5	0.06	<10	<10	68	<10	34	1
3880	2.8	2.21	54	44	<0.5	<5	0.04	1	55	14	41	6.73	<1	0.04	13	0.31	4701	3	0.01	3	1119	28	0.09	<5	2	6	<5	0.08	<10	20	68	<10	42	1
3851	7.0	1.66	50	33	<0.5	<5	0.09	1	9	15	10	4.86	1	0.04	11	0.33	317	3	0.01	6	964	41	0.05	<5	2	9	<5	0.14	<10	<10	77	<10	46	4
3826	6.0	2.01	46	39	<0.5	<5	0.07	1	15	20	29	7.46	<1	0.03	11	0.65	603	<2	0.01	16	593	115	0.04	<5	2	12	<5	0.14	<10	<10	65	<10	102	7
3799	2.0	1.50	16	34	<0.5	<5	0.05	<1	14	17	11	5.26	<1	0.05	16	0.28	623	4	0.02	10	704	55	0.06	<5	1	5	<5	0.20	<10	<10	68	<10	69	21
3776	3.6	1.67	28	57	<0.5	<5	0.05	<1	6	9	9	3.21	1	0.05	12	0.29	369	<2	0.01	5	746	17	0.05	<5	1	7	<5	0.03	<10	<10	47	<10	58	1
3751	0.5	2.17	17	57	0.8	<5	0.08	2	11	15	6	5.50	<1	0.03	<10	0.56	531	<2	0.01	14	512	12	0.04	<5	2	16	<5	0.12	<10	<10	59	<10	64	5
3723	0.4	0.81	<5	54	<0.5	<5	0.09	<1	2	3	1	0.67	<1	0.04	<10	0.05	35	<2	0.02	1	366	19	0.04	<5	<1	14	<5	0.04	<10	<10	26	<10	8	<1
3702	3.6	2.19	61	17	1.5	<5	0.04	4	7	17	22	8.85	<1	0.05	26	0.25	380	3	0.04	5	687	176	0.08	<5	2	3	5	0.14	<10	<10	41	<10	114	58
3685	<0.2	2.08	9	40	0.7	<5	0.10	2	10	15	8	4.72	<1	0.03	11	0.63	399	<2	0.01	16	391	11	0.03	<5	3	19	<5	0.12	<10	<10	57	<10	64	8
3660	<0.2	2.42	17	40	0.7	<5	0.09	2	8	18	9	4.82	<1	0.05	21	0.40	317	2	0.02	13	1339	18	0.08	<5	1	11	<5	0.07	<10	<10	52	<10	60	10
3634	0.2	2.23	11	14	1.9	<5	0.03	2	5	8	4	5.53	<1	0.06	29	0.12	236	3	0.07	3	446	17	0.06	<5	3	3	9	0.16	<10	<10	24	<10	47	467
3612	<0.2	2.34	9	40	0.7	<5	0.10	2	11	15	9	4.95	<1	0.02	10	0.64	442	<2	0.01	15	255	7	0.03	<5	3	18	<5	0.13	<10	<10	60	<10	63	10
3587	0.2	1.98	10	35	0.6	<5	0.07	1	8	12	6	3.88	1	0.02	10	0.39	331	<2	0.01	11	525	7	0.05	<5	1	16	<5	0.10	<10	<10	55	<10	44	5

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3190SJ

Date : Sep-15-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment23

Sample type: soils

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
3565	<0.2	1.75	8	56	0.8	<5	0.21	1	10	12	4	3.88	<1	0.04	12	0.55	467	6	0.02	12	701	12	0.07	<5	1	19	<5	0.09	<10	<10	49	<10	61	5
3541	0.2	2.09	18	42	0.8	<5	0.06	2	9	13	2	5.32	<1	0.04	13	0.41	428	3	0.02	9	558	30	0.05	<5	1	11	<5	0.11	<10	<10	53	<10	50	11
3523	<0.2	2.01	11	70	0.8	<5	0.22	2	12	15	9	4.15	<1	0.04	12	0.65	511	<2	0.01	18	767	13	0.03	<5	2	24	<5	0.09	<10	<10	56	<10	87	3
3499	1.9	2.07	2045	55	0.7	<5	0.12	3	23	10	45	7.40	<1	0.03	16	0.65	1478	14	0.01	15	1129	65	0.04	22	3	15	<5	0.06	<10	<10	50	<10	171	7
3470	1.7	2.99	259	77	1.1	<5	0.19	3	34	14	24	6.25	1	0.05	15	0.63	1766	5	0.01	12	1592	66	0.08	<5	2	17	<5	0.07	<10	<10	59	<10	135	4
3452	<0.2	2.01	9	50	0.7	<5	0.18	1	15	15	10	4.32	<1	0.03	<10	0.64	722	<2	0.01	18	825	10	0.02	<5	2	21	<5	0.12	<10	<10	57	<10	68	4
3428	0.7	2.51	6	90	0.9	<5	0.35	4	12	15	14	5.41	<1	0.03	10	0.57	541	<2	0.01	16	520	8	0.04	<5	2	30	<5	0.12	<10	<10	57	<10	319	4
3403	7.3	1.07	71	77	<0.5	<5	0.06	2	7	4	14	3.28	<1	0.06	12	0.21	351	2	0.01	4	988	45	0.08	<5	<1	7	<5	0.01	<10	<10	31	<10	56	2
3374	1.7	1.07	43	104	<0.5	<5	0.03	1	7	7	9	3.03	<1	0.06	<10	0.13	1555	6	0.01	6	943	55	0.06	<5	<1	6	<5	0.02	<10	<10	48	<10	48	2
3356	5.4	1.72	149	48	0.5	<5	0.03	1	9	6	118	3.32	<1	0.07	21	0.10	925	10	0.01	3	955	251	0.07	<5	1	5	<5	0.05	<10	<10	35	<10	111	2
3334	0.3	1.53	16	35	0.8	<5	0.04	1	9	11	6	4.41	<1	0.05	12	0.21	863	5	0.01	6	1346	25	0.07	<5	1	11	<5	0.13	<10	<10	56	<10	37	11
3313	1.9	0.74	199	50	<0.5	<5	0.01	2	7	4	31	4.33	<1	0.06	<10	0.06	342	9	0.01	3	1121	33	0.05	<5	<1	6	<5	0.05	<10	<10	67	<10	79	2
3285	0.2	1.94	65	46	0.5	<5	0.06	2	11	20	9	4.96	<1	0.03	<10	0.61	628	5	0.01	19	555	22	0.06	<5	1	13	<5	0.09	<10	<10	53	<10	68	8
3253	1.2	2.19	23	44	0.6	<5	0.04	2	17	15	5	6.49	<1	0.03	10	0.40	1883	5	0.01	12	568	69	0.05	<5	1	12	<5	0.11	<10	<10	62	<10	75	10
3223	2.3	3.42	56	70	<0.5	<5	0.21	2	10	19	182	4.70	<1	0.04	47	0.44	605	9	0.02	14	1440	664	0.11	<5	3	5	<5	0.05	<10	<10	30	<10	314	12
3194	1.2	3.46	15	37	<0.5	<5	0.04	<1	8	19	37	6.22	<1	0.02	35	0.24	500	2	0.02	7	739	134	0.08	<5	4	1	<5	0.10	<10	<10	33	<10	85	30
3164	0.7	1.65	7	61	<0.5	<5	0.08	<1	10	20	14	4.32	<1	0.02	<10	0.61	373	33	0.01	18	447	25	0.04	<5	1	9	<5	0.08	<10	<10	44	<10	121	5
3135	2.3	2.70	10	46	<0.5	<5	0.03	<1	12	23	14	7.73	<1	0.02	<10	0.42	1027	2	0.01	13	1495	23	0.06	<5	1	5	<5	0.11	<10	<10	86	<10	62	5
3117	6.3	1.85	649	49	<0.5	<5	<0.01	13	26	11	119	8.02	<1	0.07	13	0.31	1607	171	0.01	4	2236	355	0.03	<5	3	1	<5	0.02	<10	<10	41	<10	195	4
3085	5.0	1.80	458	86	<0.5	<5	0.02	10	51	14	137	8.65	<1	0.09	14	0.75	3839	20	0.01	17	1975	295	0.08	<5	4	2	<5	0.04	<10	18	49	<10	335	3
3053	0.8	2.33	41	48	<0.5	<5	0.11	<1	15	22	24	5.69	<1	0.03	10	0.81	755	8	0.01	25	736	28	0.03	<5	3	7	<5	0.09	<10	<10	54	<10	117	12
3028	0.8	2.31	7	35	<0.5	<5	0.02	<1	11	22	8	7.19	<1	0.01	<10	0.50	379	<2	0.01	13	503	24	0.05	<5	2	5	<5	0.14	<10	<10	57	<10	62	16
3003	0.5	2.52	9	45	<0.5	<5	0.01	<1	12	21	13	7.40	<1	0.02	<10	0.45	519	<2	0.01	14	580	29	0.05	<5	2	5	<5	0.14	<10	<10	75	<10	69	4
2981	3.4	1.62	460	63	<0.5	7	<0.01	9	36	5	25	10.34	<1	0.05	<10	0.11	4992	3	0.01	<1	2024	469	0.10	<5	1	1	<5	0.01	<10	28	46	<10	103	4
2946	0.4	1.69	51	136	<0.5	<5	0.18	1	9	23	6	5.75	<1	0.03	<10	0.51	510	<2	0.01	17	857	25	0.06	<5	<1	13	<5	0.04	<10	<10	73	<10	80	2
2925	1.6	0.79	272	99	<0.5	5	<0.01	5	13	3	24	6.61	<1	0.07	<10	0.02	4383	3	0.01	<1	2404	57	0.08	<5	<1	1	<5	0.01	<10	20	26	<10	92	2
2901	11.7	2.07	182	72	<0.5	<5	0.12	4	16	15	26	6.76	<1	0.05	17	0.19	1790	5	0.01	4	1252	114	0.09	<5	<1	6	<5	0.04	<10	<10	64	<10	139	3
2871	7.8	1.26	278	76	<0.5	<5	0.06	5	7	14	16	5.13	<1	0.05	<10	0.27	812	<2	0.01	7	2231	101	0.10	<5	<1	6	<5	0.01	<10	<10	57	<10	53	2
2856	10.5	2.57	328	62	<0.5	<5	<0.01	6	23	13	40	9.29	<1	0.06	29	0.15	3501	3	0.03	4	1115	424	0.11	<5	3	<1	<5	0.11	<10	<10	22	<10	161	44
2836	14.3	0.88	533	114	<0.5	<5	<0.01	10	19	8	30	9.32	<1	0.07	<10	0.05	3900	2	0.01	2	2565	330	0.11	<5	<1	5	<5	0.05	<10	21	58	<10	101	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3190SJ

Date : Sep-15-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment23

Sample type: soils

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
2817	10.1	1.02	353	113	<0.5	5	0.01	7	20	4	44	8.14	<1	0.07	10	0.06	1789	10	0.01	1	1626	150	0.06	<5	1	1	<5	0.01	<10	12	35	<10	109	3
2803	15.7	0.54	1617	149	<0.5	9	0.06	32	26	6	95	12.28	<1	0.07	10	0.23	1344	10	0.01	7	1999	172	0.42	<5	3	3	<5	0.01	<10	18	16	<10	157	5
2757	7.5	1.21	1429	72	<0.5	7	<0.01	28	36	13	59	10.78	<1	0.07	17	0.20	2973	<2	0.01	6	3838	119	0.04	9	3	2	<5	0.02	<10	17	50	<10	135	5
2736	43.7	1.85	3718	88	<0.5	6	0.01	77	18	4	63	8.88	<1	0.05	<10	0.13	3232	<2	0.01	<1	2429	338	0.11	33	1	2	<5	0.01	<10	18	31	<10	124	9
2705	1.0	1.42	25	26	<0.5	<5	<0.01	<1	6	10	2	3.42	<1	0.04	16	0.10	334	3	0.01	3	852	60	0.08	<5	1	2	<5	0.14	<10	<10	49	<10	37	22
2675	1.6	2.09	200	42	<0.5	<5	0.01	4	9	20	9	6.48	<1	0.03	<10	0.57	598	2	0.01	12	658	116	0.05	<5	1	5	<5	0.09	<10	<10	70	<10	82	4
2646	3.3	1.38	429	67	<0.5	<5	0.01	9	10	14	14	6.22	<1	0.05	15	0.14	933	3	0.01	3	1015	64	0.06	<5	1	5	<5	0.15	<10	<10	110	<10	48	4
2621	0.5	2.24	58	55	<0.5	<5	0.07	1	11	26	14	6.20	<1	0.06	17	0.70	468	<2	0.01	18	1005	35	0.04	<5	2	9	<5	0.11	<10	<10	62	<10	89	11
2589	2.9	1.18	361	36	<0.5	<5	<0.01	7	8	12	6	6.76	<1	0.05	15	0.08	401	3	0.02	2	1451	46	0.07	<5	1	3	<5	0.16	<10	<10	80	<10	46	16
2565	3.5	0.75	268	55	<0.5	<5	<0.01	5	5	4	14	4.23	<1	0.07	17	0.07	222	<2	0.01	2	1089	22	0.04	<5	1	7	<5	0.01	<10	<10	78	<10	64	1
2549	17.7	3.14	593	54	<0.5	<5	<0.01	11	14	16	22	9.68	<1	0.05	16	0.50	824	<2	0.01	5	1496	102	0.09	5	2	2	<5	0.04	<10	<10	74	<10	116	6
2532	0.5	3.57	19	35	<0.5	<5	0.03	<1	9	30	17	7.37	<1	0.03	13	0.40	526	<2	0.01	13	1003	26	0.06	<5	2	5	<5	0.09	<10	<10	50	<10	67	8
2504	3.1	2.18	103	43	<0.5	<5	0.07	2	10	22	21	5.85	<1	0.05	15	0.57	469	<2	0.01	16	1339	145	0.08	<5	1	8	<5	0.07	<10	<10	62	<10	101	5
2470	0.7	1.83	11	47	<0.5	<5	0.08	<1	12	24	11	6.37	<1	0.03	<10	0.51	585	<2	0.01	19	1252	22	0.05	<5	2	11	<5	0.11	<10	<10	69	<10	74	3
2465	4.3	1.03	67	40	<0.5	<5	0.02	1	4	8	8	2.73	<1	0.06	11	0.06	215	2	0.01	3	997	47	0.08	<5	<1	6	<5	0.06	<10	<10	39	<10	42	1
2443	2.2	2.53	72	156	<0.5	<5	0.34	4	31	25	44	6.23	<1	0.08	29	0.96	2204	<2	0.02	30	1459	101	0.05	<5	4	19	<5	0.06	<10	12	60	<10	520	3
2422	6.7	1.60	289	56	<0.5	<5	<0.01	5	13	17	28	11.34	<1	0.09	16	0.47	1139	<2	0.01	5	3047	149	0.08	<5	3	3	<5	0.06	<10	13	72	<10	110	5
2396	0.9	2.17	41	114	<0.5	<5	0.27	1	21	28	37	5.54	<1	0.07	19	1.04	1130	<2	0.01	35	1328	41	0.01	<5	5	16	<5	0.08	<10	12	60	<10	161	3
2371	1.4	2.66	66	87	<0.5	<5	0.12	1	16	27	28	5.95	<1	0.06	19	0.82	926	7	0.01	22	1499	48	0.04	<5	3	11	<5	0.10	<10	<10	69	<10	124	4
2348	0.5	2.03	14	59	<0.5	<5	0.10	<1	10	27	13	4.06	<1	0.04	13	0.72	387	<2	0.01	20	885	23	0.02	<5	2	12	<5	0.08	<10	<10	63	<10	86	2
2324	3.2	1.88	268	65	<0.5	5	0.01	5	43	16	21	9.91	<1	0.04	<10	0.21	3910	<2	0.01	3	2323	106	0.09	<5	1	3	<5	0.05	<10	20	111	<10	75	3
2303	2.5	1.91	40	35	<0.5	<5	0.02	1	6	16	9	3.87	<1	0.03	<10	0.30	227	<2	0.01	10	937	15	0.08	<5	<1	6	<5	0.05	<10	<10	42	<10	44	1
2281	<0.2	2.17	16	47	<0.5	<5	0.02	<1	6	27	6	3.80	<1	0.04	15	0.37	197	<2	0.01	12	613	20	0.04	<5	1	8	<5	0.07	<10	<10	71	<10	47	2
2254	1.1	3.38	30	69	<0.5	<5	0.14	<1	38	31	45	7.48	<1	0.08	39	0.62	3475	2	0.02	16	2148	54	0.07	<5	4	8	<5	0.15	<10	10	88	<10	161	7
2224	0.8	3.00	38	52	<0.5	<5	0.05	<1	26	26	20	7.37	<1	0.06	16	0.40	2785	4	0.01	11	2260	33	0.10	<5	2	5	<5	0.09	<10	11	67	<10	89	5
2196	1.2	1.04	6	40	<0.5	<5	0.01	<1	5	11	3	2.21	<1	0.03	11	0.09	154	<2	0.01	5	691	14	0.06	<5	1	5	<5	0.07	<10	<10	45	<10	27	3
2169	<0.2	1.97	89	53	<0.5	<5	0.02	1	7	24	17	7.95	<1	0.03	<10	0.39	287	<2	0.01	8	970	22	0.09	<5	1	8	<5	0.06	<10	<10	100	<10	48	3
2145	1.5	1.01	13	54	<0.5	<5	0.01	<1	3	12	4	1.79	<1	0.08	20	0.14	131	2	0.01	2	1078	45	0.05	<5	<1	4	<5	0.05	<10	<10	39	<10	24	1
2127	0.3	1.63	7	41	<0.5	<5	0.05	<1	6	14	7	2.50	<1	0.05	10	0.22	202	2	<0.01	6	688	26	0.05	<5	1	9	<5	0.06	<10	<10	49	<10	42	1
2114	0.9	1.22	5	52	<0.5	<5	0.09	<1	5	11	13	1.69	<1	0.06	15	0.19	194	2	<0.01	5	1144	60	0.12	<5	1	8	<5	0.06	<10	<10	30	<10	98	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3190SJ

Date : Sep-15-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment23

Sample type: soils

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
2112	0.3	2.28	24	65	<0.5	<5	0.10	<1	13	22	17	4.63	<1	0.04	12	0.67	483	<2	<0.01	17	788	24	0.03	<5	2	11	<5	0.08	<10	<10	61	<10	87	2
2109	0.4	2.00	19	67	<0.5	<5	0.11	<1	19	24	24	5.23	<1	0.05	14	0.81	1038	<2	<0.01	26	1221	25	0.02	<5	3	11	<5	0.08	<10	<10	58	<10	117	3
2107	0.3	2.37	20	84	<0.5	<5	0.20	<1	20	28	23	4.96	<1	0.05	13	0.89	974	<2	<0.01	30	693	22	0.03	<5	3	18	<5	0.08	<10	<10	59	<10	118	2
2102	0.4	2.39	21	108	<0.5	<5	0.12	<1	19	31	27	4.78	<1	0.06	13	0.85	997	<2	<0.01	32	1131	21	0.02	<5	3	12	<5	0.06	<10	<10	62	<10	123	1
2090	0.6	1.80	26	121	<0.5	<5	0.23	<1	21	27	39	4.96	<1	0.05	14	0.95	1129	<2	<0.01	39	1106	23	<0.01	<5	5	14	<5	0.06	<10	<10	51	<10	128	2
2075	0.4	1.83	21	71	<0.5	<5	0.22	<1	20	27	35	4.64	<1	0.04	13	0.92	894	<2	<0.01	41	1022	18	<0.01	<5	5	13	<5	0.06	<10	<10	48	<10	126	2
2042	<0.2	3.80	23	71	<0.5	<5	0.07	<1	16	32	20	6.40	<1	0.04	54	0.52	879	6	<0.01	25	2074	26	0.09	<5	3	4	<5	0.06	<10	19	54	<10	151	7
2013	0.5	2.39	15	74	<0.5	<5	0.09	<1	16	27	21	4.52	<1	0.04	21	0.78	563	2	<0.01	30	877	22	0.03	<5	3	8	<5	0.06	<10	<10	51	<10	120	4
1979	0.4	2.48	23	131	<0.5	<5	0.22	<1	17	29	20	4.62	<1	0.05	19	0.83	727	<2	<0.01	34	1243	21	0.03	<5	4	13	<5	0.06	<10	<10	49	<10	173	3
1949	0.3	1.45	6	34	<0.5	<5	0.02	<1	8	16	4	4.79	<1	0.04	19	0.16	688	4	0.01	5	725	40	0.07	<5	1	3	<5	0.13	<10	<10	43	<10	47	22
1920	0.3	1.82	8	64	<0.5	<5	0.02	<1	9	17	7	4.54	<1	0.04	13	0.17	836	3	<0.01	6	671	21	0.05	<5	1	6	<5	0.06	<10	<10	70	<10	48	2
1882	1.2	3.35	20	48	<0.5	<5	0.02	<1	14	20	17	5.73	<1	0.06	29	0.18	1079	3	0.03	7	1274	31	0.12	<5	1	<1	<5	0.05	<10	<10	27	<10	77	11
1859	0.9	2.01	13	69	<0.5	<5	0.03	<1	13	23	10	5.20	<1	0.04	<10	0.46	960	<2	<0.01	14	646	20	0.05	<5	1	8	<5	0.06	<10	<10	64	<10	67	2
1829	0.3	2.61	18	73	<0.5	<5	0.09	<1	13	24	21	4.26	<1	0.04	10	0.77	550	<2	<0.01	25	687	17	0.04	<5	2	9	<5	0.06	<10	<10	44	<10	95	1
1782	0.2	2.99	6	87	<0.5	<5	0.03	<1	9	24	9	4.90	<1	0.04	24	0.33	560	2	<0.01	10	630	21	0.06	<5	2	5	<5	0.08	<10	<10	37	<10	80	16

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Quality Assaying for over 25 Years

Assay Certificate

8V-3215-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment24**
Attn: **Sue Deane**

Sep-25-08

We hereby certify the following assay of 22 core samples submitted Sep-08-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120629	0.11	0.07	1.5
120630	0.14		2.1
120631	0.14		1.3
120632	0.10		2.6
120633	0.17		3.3
120634	0.42		3.5
120635	0.24		4.3
120636	0.53		8.3
120637	0.29		7.4
120638	0.17	0.17	9.7
120639	0.10		2.4
120640	0.12		2.2
120641	0.13		1.9
120642	0.25		2.5
120643	0.20		3.0
120644	0.10		2.3
120645	0.71		3.8
120646	0.11		3.0
120685	0.24		1.1
120686	0.20	0.20	0.6
120687	0.34		1.3
120688	0.34		1.3
*0211	2.23		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3215-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment24**
Attn: **Sue Deane**

Sep-25-08

We hereby certify the following assay of 22 core samples submitted Sep-08-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120689	0.48	0.59	1.0
120690	0.59		1.4
120691	0.33		1.6
120692	0.34		1.9
120693	0.26		2.8
120694	0.65		3.0
120695	0.52		2.3
120696	0.53		1.6
120697	0.81		2.1
120698	0.53	0.57	2.0
120699	0.61		3.5
120700	0.01		<0.1
120701	0.51		3.6
120702	0.76		3.0
120703	0.49		3.4
120704	0.14		2.7
120705	0.10		2.4
120706	0.18		2.9
120707	0.02		<0.1
120708	0.31	0.32	3.1
120709	0.45		3.2
120710	0.21		1.8
*0211	2.20		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3215-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment24**
Attn: **Sue Deane**

Sep-25-08

We hereby certify the following assay of 22 core samples submitted Sep-08-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
120711	0.03	0.04	0.3	
120712	0.11		1.3	
120713	0.31		1.6	
120714	0.62		3.7	
120715	0.99		3.9	
120716	0.52		1.6	
120717	0.45		2.7	
120718	0.35		1.8	
120719	0.42		1.6	
120720	0.55	0.58	2.0	
120721	0.15		2.2	
120722	0.33		2.4	
120723	0.21		1.8	
120724	0.22		2.9	
120725	0.10		>200	803.7
120726	0.31		4.4	
120727	0.45		6.7	
120728	0.10		3.6	
120729	0.02		1.2	
120730	0.01	0.01	2.1	
120731	0.03		2.3	
120732	0.02		1.2	
*0211	2.14			
*CCu-1c				128.4
*BLANK	<0.01			<0.1

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3215-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment24**
Attn: **Sue Deane**

Sep-25-08

We hereby certify the following assay of 22 core samples submitted Sep-08-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120733	0.15	0.12	2.2
120734	0.21		3.2
120735	0.29		2.0
120736	0.35		2.2
120737	0.12		1.6
120738	0.13		7.6
120739	0.08		1.6
120740	0.08		1.5
120741	0.13		2.7
120742	0.17	0.14	1.8
120743	0.13		1.6
120744	0.12		2.2
120745	0.34		2.9
120746	0.17		2.5
120747	0.15		2.4
120748	0.17		3.2
120749	0.12		2.1
120750	0.01		<0.1
120751	0.16		2.1
120752	0.25	0.26	2.2
120753	0.19		2.0
120754	0.13		3.8
*0211	2.18		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3215-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment24**
Attn: **Sue Deane**

Sep-25-08

We hereby certify the following assay of 22 core samples submitted Sep-08-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120755	0.05	0.04	1.9
120756	0.29		2.1
120757	0.26		23.9
120758	0.32		2.9
120759	0.67		1.7
120760	0.45		2.0
120761	0.09		0.6
120762	0.03		0.9
120763	0.06		1.1
120764	0.33	0.33	2.2
120765	0.26		2.5
120766	0.43		2.8
120767	0.23		1.0
120768	0.05		1.1
120769	0.07		7.0
120770	0.13		1.7
120771	0.02		1.0
120772	0.04		0.9
120773	0.03		0.6
125774	0.01	<0.01	<0.1
125775	5.99		3.0
125776	0.02		1.2
*0211	2.22		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3215-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment24**
Attn: **Sue Deane**

Sep-25-08

We hereby certify the following assay of 22 core samples submitted Sep-08-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
125777	0.01	0.01	<0.1
125778	0.04		1.8
125779	0.04		1.6
125780	0.09		4.0
125781	0.15		3.0
125782	0.01		<0.1
125783	0.58		3.4
125784	2.84		4.0
125785	0.13		2.8
125786	0.11	0.12	3.5
125787	0.06		1.6
125788	0.08		1.6
125789	0.17		3.8
125790	0.24		3.4
125791	0.08		1.7
125792	0.06		<0.1
125793	0.04		1.6
125794	0.11		2.2
125795	71.52		80.9
125796	0.27	0.25	2.4
125797	0.30		2.0
125798	0.04		1.2
*0211	2.17		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3215-RA7

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment24**
Attn: **Sue Deane**

Sep-25-08

We hereby certify the following assay of 22 core samples submitted Sep-08-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
125799	0.03	0.06	1.3
125800	<0.01		<0.1
125801	0.06		1.6
125802	0.08		0.9
125803	0.08		1.2
125804	0.04		1.3
125805	0.18		2.6
125806	0.01		<0.1
125807	0.29		3.9
125808	0.63	0.71	3.3
125809	0.13		8.6
125810	0.33		4.7
125811	1.44		5.5
125812	0.43		3.1
125813	0.18		3.2
125814	0.50		5.0
125815	0.23		3.5
125816	0.26		3.9
125817	<0.01		<0.1
125818	0.17	0.14	3.4
125819	0.29		8.4
125820	0.25		4.6
*0211	2.15		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3215-RA8

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment24**
Attn: **Sue Deane**

Sep-25-08

We hereby certify the following assay of 22 core samples submitted Sep-08-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
125821	0.05	0.06	2.1	
125822	0.23		4.1	
125823	0.18		4.5	
125824	0.18		5.2	
125825	0.11		>200	765.3
125826	0.31		6.4	
125827	0.15		5.4	
125828	0.14		3.1	
125829	0.02		2.0	
125830	0.09	0.07	2.5	
125831	0.06		3.4	
125832	0.18		8.1	
125833	0.20		8.8	
125914	0.02		0.2	
125915	0.04		1.3	
125916	0.03		1.6	
125857	0.26		6.6	
125866	0.31		4.2	
125870	0.86		>200	436.5
125898	0.22	0.20	6.5	
125945	0.05		4.1	
125946	0.06		0.9	
*0211	2.26			
*CCu-1c				128.4
*BLANK	<0.01			<0.1

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3215-RA9

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment24**
Attn: **Sue Deane**

Sep-25-08

We hereby certify the following assay of 22 core samples submitted Sep-08-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
125947	0.05	0.06	0.9
125948	0.02		0.5
125949	0.01		0.5
125950	<0.01		<0.1
139478	0.06		1.0
139479	0.02		0.6
139480	0.04		0.6
139481	0.12		0.3
139482	0.13		0.5
139483	0.04	0.03	0.6
139484	0.03		0.6
139485	0.02		0.8
139486	0.05		0.8
139487	0.10		0.9
139488	0.02		1.2
139489	0.01		0.7
139520	0.21		3.0
139521	0.70		4.2
139522	0.26		7.0
139523	0.42	0.38	4.6
139524	0.50		5.0
139525	0.33		4.5
*0211	2.12		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3215-RA10

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment24**
Attn: **Sue Deane**

Sep-25-08

We hereby certify the following assay of 5 core samples submitted Sep-08-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
139526	0.45	0.44	3.8
139527	0.37		2.6
139528	0.30		1.9
139529	0.16		2.4
SD08-20	0.01		<0.1
*0211	2.11		
*BLANK	<0.01		

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3215RJ

Date : Sep-25-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment24

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120629	1.5	2.37	37	89	<0.5	<5	5.92	1	15	16	101	5.67	<1	0.24	<10	1.44	2592	7	0.01	2	1293	10	0.78	<5	4	225	<5	0.01	<10	12	82	<10	156	2
120630	2.1	2.23	70	125	<0.5	<5	5.58	2	17	18	96	5.61	<1	0.38	<10	1.27	2695	8	0.01	3	1265	94	1.47	<5	3	140	<5	<0.01	<10	13	65	<10	222	2
120631	1.3	1.73	81	140	<0.5	<5	8.82	3	14	31	44	4.19	<1	0.40	<10	0.82	2905	4	0.01	2	1191	43	1.20	<5	3	200	<5	<0.01	<10	12	39	<10	166	1
120632	2.6	1.83	85	144	<0.5	<5	7.20	2	14	18	122	4.81	<1	0.31	<10	0.98	2460	9	0.01	2	1102	29	1.21	<5	3	182	<5	<0.01	<10	10	58	<10	144	1
120633	3.3	1.77	217	119	<0.5	<5	7.53	7	17	13	167	4.97	<1	0.28	<10	0.94	2857	9	0.01	2	1167	171	1.31	<5	4	152	<5	<0.01	<10	13	69	<10	443	1
120634	3.5	2.09	765	121	<0.5	<5	4.95	16	21	16	164	5.79	<1	0.26	<10	1.26	3102	8	0.01	3	1399	173	1.27	<5	6	125	<5	<0.01	<10	13	110	<10	240	2
120635	4.3	2.00	572	97	<0.5	<5	4.54	14	22	16	215	6.24	<1	0.23	<10	1.11	2755	11	0.01	3	1453	99	2.22	<5	5	113	<5	<0.01	<10	12	103	<10	427	2
120636	8.3	2.06	380	122	<0.5	<5	3.11	67	25	26	332	6.22	1	0.29	<10	1.23	2620	10	0.01	4	1550	1306	2.90	<5	5	83	<5	0.01	<10	12	102	96	8462	2
120637	7.4	1.63	430	113	<0.5	<5	5.64	59	18	26	303	5.57	<1	0.19	<10	0.94	2987	8	0.01	3	1216	1661	2.57	<5	5	158	<5	<0.01	<10	13	91	58	5156	2
120638	9.7	1.29	239	84	<0.5	<5	6.19	79	18	34	380	6.78	<1	0.28	10	0.70	3266	6	0.01	2	1126	2694	>5.00	<5	3	159	<5	0.01	<10	18	43	70	6335	2
120639	2.4	0.71	175	135	<0.5	<5	4.71	4	12	44	11	3.53	<1	0.31	<10	0.29	2750	6	0.01	3	840	90	3.14	<5	1	141	<5	0.01	<10	11	16	<10	156	1
120640	2.2	1.21	160	120	<0.5	<5	2.94	4	13	36	73	4.32	<1	0.30	<10	0.70	2572	20	0.01	2	992	93	2.76	<5	2	83	<5	0.01	<10	10	35	<10	254	1
120641	1.9	1.04	145	125	<0.5	<5	2.05	4	12	53	56	3.76	<1	0.28	<10	0.62	2331	7	0.01	2	921	132	2.56	<5	1	64	<5	0.02	<10	<10	29	<10	325	1
120642	2.5	0.83	182	111	<0.5	<5	7.38	5	11	41	29	3.40	<1	0.24	<10	0.46	2974	6	0.01	2	808	494	2.64	<5	2	164	<5	0.03	<10	12	22	<10	274	1
120643	3.0	2.08	213	80	<0.5	<5	5.38	6	18	22	90	5.92	<1	0.20	<10	1.40	3361	8	0.01	2	1189	226	2.19	<5	4	114	<5	0.09	<10	16	80	<10	374	2
120644	2.3	2.27	62	113	<0.5	<5	4.58	2	25	9	162	5.62	<1	0.30	11	1.21	2340	7	0.02	2	1554	39	0.76	<5	6	125	<5	0.13	<10	10	96	<10	175	2
120645	3.8	2.07	99	95	<0.5	<5	4.33	2	25	11	196	5.92	<1	0.28	10	1.10	2323	7	0.02	2	1471	45	1.71	<5	5	117	<5	0.13	<10	10	93	<10	170	2
120646	3.0	2.19	37	149	<0.5	<5	4.64	2	25	9	188	5.27	<1	0.38	12	1.06	2366	5	0.03	2	1588	15	0.89	<5	6	131	<5	0.14	<10	<10	93	<10	227	2
120685	1.1	1.82	19	56	<0.5	<5	5.72	7	29	207	210	4.00	1	0.12	<10	1.59	1205	46	0.03	27	1501	18	0.30	<5	8	133	<5	0.15	<10	<10	132	<10	401	3
120686	0.6	1.73	12	65	<0.5	<5	3.18	3	25	163	187	3.64	<1	0.15	<10	1.70	752	49	0.04	23	1535	8	0.17	<5	5	112	<5	0.15	<10	<10	108	<10	236	2
120687	1.3	1.57	13	62	<0.5	<5	2.68	6	25	186	281	3.72	<1	0.11	<10	1.58	851	56	0.03	25	1526	147	0.24	<5	5	107	<5	0.15	<10	<10	109	<10	395	3
120688	1.3	1.63	17	48	<0.5	<5	4.60	4	28	196	317	3.91	<1	0.08	<10	1.55	1112	72	0.03	26	1520	44	0.34	<5	7	141	<5	0.14	<10	<10	117	<10	262	4
120689	1.0	1.20	13	42	<0.5	<5	3.17	1	24	160	308	2.93	<1	0.06	<10	1.13	711	76	0.02	23	1166	10	0.31	<5	5	100	<5	0.12	<10	<10	92	<10	107	2
120690	1.4	1.15	13	49	<0.5	<5	2.52	1	22	134	312	3.08	<1	0.06	<10	1.16	746	64	0.03	21	1144	11	0.39	<5	6	117	<5	0.10	<10	<10	92	<10	121	3
120691	1.6	1.09	16	48	<0.5	<5	2.98	6	20	131	240	2.87	<1	0.06	<10	1.07	880	44	0.03	19	1041	97	0.48	<5	5	146	<5	0.09	<10	<10	69	<10	361	3
120692	1.9	1.18	17	98	<0.5	<5	2.47	13	20	130	282	3.29	1	0.06	<10	1.01	747	31	0.03	19	1173	131	0.67	<5	4	114	<5	0.10	<10	<10	74	<10	706	3
120693	2.8	1.28	42	55	<0.5	<5	6.06	3	25	117	205	5.53	<1	0.09	<10	2.00	2383	51	0.01	23	1010	81	0.98	<5	17	279	<5	0.03	<10	11	91	<10	285	2
120694	3.0	1.53	27	99	<0.5	<5	4.93	2	27	178	340	4.64	<1	0.18	<10	1.44	1998	69	0.02	26	1077	14	0.34	<5	11	129	<5	0.10	<10	<10	131	<10	262	3
120695	2.3	1.71	45	37	<0.5	<5	5.93	3	25	184	269	4.79	<1	0.05	<10	1.51	2248	52	0.02	29	1085	91	0.32	<5	9	118	<5	0.10	<10	<10	137	<10	310	3
120696	1.6	1.70	22	45	<0.5	<5	3.31	2	29	198	280	4.94	<1	0.08	<10	1.65	1393	36	0.03	29	1108	10	0.12	<5	7	69	<5	0.13	<10	<10	139	<10	277	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3215RJ

Date : Sep-25-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment24

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120697	2.1	1.39	20	49	<0.5	<5	2.79	3	27	182	340	4.09	1	0.07	<10	1.35	1208	84	0.03	26	1097	26	0.21	<5	7	84	<5	0.11	<10	<10	119	<10	317	2
120698	2.0	1.47	43	54	<0.5	<5	5.11	4	26	191	245	4.29	<1	0.09	<10	1.21	1891	97	0.02	26	1006	187	0.20	<5	10	100	<5	0.11	<10	<10	138	<10	308	2
120699	3.5	1.42	64	33	<0.5	<5	10.65	12	25	219	213	4.21	1	0.05	<10	0.75	3210	86	0.01	27	1009	73	0.48	<5	19	168	<5	0.06	<10	<10	160	10	645	2
120700	<0.2	0.89	<5	221	<0.5	<5	0.50	<1	8	101	<1	1.82	<1	0.39	<10	0.55	576	<2	0.06	5	624	3	<0.01	<5	2	46	<5	0.11	<10	<10	35	<10	50	1
120701	3.6	1.56	123	36	<0.5	<5	9.74	6	30	241	259	4.35	<1	0.07	<10	0.96	3055	87	<0.01	32	1194	27	0.65	<5	20	142	<5	0.06	<10	<10	179	<10	404	2
120702	3.0	2.30	35	40	<0.5	<5	8.23	4	35	271	293	5.86	1	0.06	<10	1.54	2753	50	0.01	40	1240	12	0.32	<5	24	133	<5	0.10	<10	<10	212	<10	496	3
120703	3.4	2.31	43	40	<0.5	<5	9.75	6	32	274	297	5.39	1	0.06	<10	1.79	3159	24	0.01	33	1327	120	0.31	<5	25	177	<5	0.07	<10	<10	208	11	574	2
120704	2.7	1.82	333	37	<0.5	<5	9.47	12	34	224	209	4.67	1	0.05	<10	1.39	3674	17	<0.01	30	1082	43	0.77	<5	18	198	<5	0.01	<10	<10	169	<10	540	1
120705	2.4	2.09	79	36	<0.5	<5	8.85	4	34	278	205	5.18	<1	0.05	<10	1.44	3024	37	0.01	34	1345	10	0.51	<5	24	158	<5	0.08	<10	<10	203	<10	269	2
120706	2.9	2.05	88	71	<0.5	<5	9.09	4	36	251	288	5.47	1	0.11	<10	1.32	3331	18	0.02	40	1242	120	0.74	<5	23	194	<5	0.03	<10	<10	195	<10	242	2
120707	<0.2	0.98	<5	190	<0.5	<5	2.68	<1	7	34	6	1.84	<1	0.26	15	0.56	587	<2	0.03	3	750	36	0.10	<5	2	159	<5	<0.01	<10	<10	15	<10	56	3
120708	3.1	1.87	271	56	<0.5	<5	9.02	8	28	220	280	4.68	1	0.10	<10	1.46	3034	27	0.02	29	1263	89	0.70	<5	17	139	<5	0.10	<10	<10	165	<10	344	2
120709	3.2	1.63	742	60	<0.5	<5	5.19	21	29	216	228	4.41	1	0.10	<10	1.40	2013	35	0.02	30	1301	126	1.11	8	11	112	<5	0.08	<10	<10	137	<10	624	2
120710	1.8	2.17	60	156	<0.5	<5	6.02	2	33	239	187	5.35	<1	0.42	<10	1.56	2379	31	0.07	35	1333	38	0.62	<5	17	136	<5	0.09	<10	<10	167	<10	184	3
120711	0.3	1.36	7	605	<0.5	<5	3.37	<1	20	192	30	3.28	1	0.10	<10	1.13	1297	21	0.03	26	1363	5	0.12	<5	7	158	<5	0.11	<10	<10	100	<10	75	2
120712	1.3	1.36	19	190	<0.5	<5	4.44	2	24	173	172	3.50	<1	0.06	<10	1.04	1615	30	0.02	26	1240	59	0.37	<5	8	229	<5	0.10	<10	<10	79	<10	235	2
120713	1.6	1.33	26	101	<0.5	<5	5.34	3	26	153	196	2.90	<1	0.06	<10	1.18	1201	28	0.01	21	1143	82	0.14	<5	6	285	<5	0.08	<10	<10	77	<10	260	2
120714	3.7	2.25	54	147	<0.5	<5	5.90	7	31	229	343	5.82	1	0.11	<10	1.55	2754	41	0.01	29	1162	382	0.54	<5	15	147	<5	0.08	<10	12	141	<10	623	2
120715	3.9	2.15	58	101	<0.5	<5	7.48	5	24	172	262	4.68	1	0.19	<10	1.59	2984	49	0.01	19	1078	77	0.43	<5	15	216	<5	0.01	<10	<10	137	<10	389	1
120716	1.6	1.98	25	140	<0.5	<5	1.78	1	18	33	165	4.46	<1	0.36	12	0.93	1389	54	0.01	8	488	18	0.24	<5	4	63	<5	<0.01	<10	<10	38	<10	182	1
120717	2.7	1.73	161	112	<0.5	<5	3.61	4	15	44	198	4.67	<1	0.26	<10	0.80	1707	28	<0.01	7	327	19	1.15	<5	4	72	<5	<0.01	<10	<10	43	<10	114	1
120718	1.8	1.61	44	187	<0.5	<5	2.02	1	15	38	175	4.05	<1	0.31	<10	0.77	1503	37	<0.01	6	335	12	0.50	<5	4	65	<5	<0.01	<10	<10	37	<10	145	1
120719	1.6	1.49	23	125	<0.5	<5	2.24	1	11	33	126	3.44	<1	0.31	<10	0.76	1638	52	0.01	3	386	32	0.39	<5	3	65	<5	0.01	<10	<10	42	<10	174	1
120720	2.0	1.42	36	142	<0.5	<5	2.13	1	18	32	178	3.81	<1	0.29	<10	0.72	1629	43	0.01	7	574	14	0.41	<5	4	71	<5	<0.01	<10	<10	48	<10	144	1
120721	2.2	1.22	20	566	0.5	<5	4.52	1	17	11	202	4.43	<1	0.33	<10	0.83	2107	28	0.01	4	969	16	0.52	<5	4	230	<5	<0.01	<10	<10	44	<10	180	1
120722	2.4	1.74	19	318	0.7	<5	3.26	1	14	8	181	3.81	<1	0.38	11	0.83	1696	19	0.01	3	1115	38	0.33	<5	2	144	<5	<0.01	<10	<10	34	<10	154	1
120723	1.8	0.70	25	168	0.5	<5	4.31	1	16	8	164	4.19	<1	0.38	<10	0.79	1872	25	0.01	2	1218	14	0.57	<5	3	199	<5	<0.01	<10	<10	26	<10	154	1
120724	2.9	1.93	158	132	<0.5	<5	4.50	9	20	7	231	5.30	<1	0.30	<10	0.95	2186	37	0.01	3	1252	110	0.96	<5	4	125	<5	<0.01	<10	11	75	<10	692	1
120725	>200.0	0.83	468	214	<0.5	139	0.61	19	8	156	7518	2.43	6	0.22	<10	0.58	320	458	0.06	8	372	996	1.26	1296	2	87	<5	0.05	<10	<10	25	<10	1042	2
120726	4.4	2.24	52	129	<0.5	<5	5.65	29	20	5	238	5.63	1	0.27	<10	1.20	2545	30	0.01	3	1182	278	1.15	<5	5	140	<5	<0.01	<10	12	85	28	2852	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3215RJ

Date : Sep-25-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment24

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120727	6.7	2.02	89	122	<0.5	<5	4.58	22	21	14	337	5.29	<1	0.26	<10	1.14	2217	21	0.01	4	1073	68	1.07	<5	4	113	<5	<0.01	<10	12	74	20	2066	1
120728	3.6	2.27	65	99	<0.5	<5	6.83	12	20	79	212	5.28	<1	0.25	<10	1.42	2833	11	0.01	11	1152	24	0.65	<5	8	162	<5	<0.01	<10	13	91	11	1048	1
120729	1.2	2.10	60	69	<0.5	<5	9.50	3	23	193	49	4.06	<1	0.13	<10	1.87	2657	2	0.01	28	1104	21	0.41	<5	15	253	<5	<0.01	<10	<10	129	<10	139	1
120730	2.1	0.55	110	60	0.6	<5	10.35	3	25	66	98	5.27	<1	0.19	<10	1.67	3558	3	0.01	29	1144	26	1.19	<5	18	556	<5	<0.01	<10	19	54	<10	105	1
120731	2.3	2.68	60	32	<0.5	<5	10.82	1	20	205	44	5.67	<1	0.10	<10	2.40	2925	8	0.01	28	1206	20	1.01	<5	16	267	<5	<0.01	<10	13	142	<10	92	2
120732	1.2	2.39	56	69	<0.5	<5	7.02	1	25	219	55	5.28	1	0.13	<10	2.20	2231	5	0.01	33	1338	35	0.82	<5	18	221	<5	<0.01	<10	<10	159	<10	92	2
120733	2.2	1.40	87	125	<0.5	<5	5.70	4	23	90	110	5.59	1	0.29	<10	1.37	2146	5	0.01	21	1277	65	1.88	<5	8	214	<5	<0.01	<10	11	69	<10	318	2
120734	3.2	1.57	338	115	<0.5	5	6.18	11	15	43	124	5.94	1	0.25	<10	0.82	2436	11	0.01	7	853	44	2.04	<5	6	163	<5	<0.01	<10	16	67	<10	399	2
120735	2.0	0.78	227	57	<0.5	<5	9.16	6	7	70	34	3.35	<1	0.11	<10	0.48	3171	3	0.01	3	390	54	1.25	<5	3	471	<5	<0.01	<10	17	31	<10	103	<1
120736	2.2	1.38	229	222	<0.5	<5	4.51	7	15	27	60	5.36	<1	0.29	<10	0.99	2407	9	0.01	3	1015	69	1.72	<5	3	167	<5	<0.01	<10	15	56	<10	255	2
120737	1.6	0.60	154	197	<0.5	<5	3.48	4	19	49	74	4.83	<1	0.31	<10	1.07	1843	12	0.01	3	977	45	1.50	<5	4	187	<5	<0.01	<10	11	27	<10	162	1
120738	7.6	1.50	101	176	<0.5	5	1.36	54	22	34	282	5.81	<1	0.35	<10	1.08	1928	5	0.01	4	1084	965	2.02	<5	4	69	<5	<0.01	<10	10	55	51	5611	2
120739	1.6	1.60	133	162	<0.5	<5	3.01	5	19	22	51	5.52	<1	0.36	<10	0.97	2219	5	0.01	3	1176	86	1.16	<5	3	125	<5	<0.01	<10	13	50	<10	371	2
120740	1.5	0.54	91	297	0.6	<5	4.18	3	20	25	51	5.32	<1	0.35	<10	1.16	2228	11	0.01	4	1089	43	1.33	<5	4	258	<5	<0.01	<10	16	24	<10	243	1
120741	2.7	0.60	92	197	0.6	<5	3.07	3	21	45	169	6.07	<1	0.38	<10	1.13	2097	13	0.01	4	1093	46	1.89	<5	5	231	<5	<0.01	<10	14	26	<10	257	2
120742	1.8	2.04	48	367	<0.5	<5	2.13	4	15	21	104	6.37	<1	0.50	<10	1.46	2634	15	0.01	2	1074	29	1.23	<5	6	85	<5	0.01	<10	14	75	<10	496	2
120743	1.6	2.06	61	215	<0.5	<5	2.01	3	17	30	92	5.46	<1	0.39	<10	1.36	2107	13	0.02	3	1090	106	1.07	<5	5	76	<5	0.01	<10	10	75	<10	354	2
120744	2.2	1.98	36	197	<0.5	<5	4.12	5	15	13	158	5.38	<1	0.38	<10	1.27	2744	10	0.01	2	1138	48	0.61	<5	5	136	<5	<0.01	<10	12	76	<10	619	1
120745	2.9	1.75	46	170	<0.5	<5	3.79	3	14	22	256	4.43	<1	0.34	11	0.88	2403	21	0.01	2	1103	13	0.58	<5	4	97	<5	0.01	<10	<10	66	<10	345	1
120746	2.5	2.09	121	137	<0.5	<5	2.64	5	23	15	184	6.16	<1	0.34	<10	1.22	2437	45	0.01	3	1186	15	2.16	<5	4	79	<5	<0.01	<10	13	84	<10	361	2
120747	2.4	2.07	163	103	<0.5	<5	2.64	4	22	22	163	6.34	<1	0.32	<10	1.21	2651	97	0.01	3	1245	21	2.39	<5	4	79	<5	<0.01	<10	14	79	<10	151	2
120748	3.2	1.94	190	134	<0.5	<5	2.69	5	22	14	208	6.24	<1	0.35	<10	1.10	2309	34	0.01	4	1253	47	2.80	<5	3	94	<5	<0.01	<10	14	68	<10	226	2
120749	2.1	2.14	58	222	<0.5	<5	4.71	2	19	10	141	5.50	<1	0.34	<10	1.16	2634	31	0.01	3	1188	11	0.98	<5	4	149	<5	0.01	<10	13	73	<10	195	1
120750	<0.2	1.00	<5	265	<0.5	<5	0.56	<1	9	119	1	2.23	<1	0.49	<10	0.62	631	<2	0.07	7	708	4	<0.01	<5	2	52	<5	0.13	<10	<10	41	<10	53	2
120751	2.1	2.01	115	116	<0.5	<5	4.16	4	20	8	180	5.13	<1	0.38	<10	1.02	2357	29	0.01	3	1285	13	0.86	<5	4	183	<5	<0.01	<10	13	64	<10	217	1
120752	2.2	2.16	46	98	<0.5	<5	4.71	2	19	9	163	5.73	<1	0.30	<10	1.06	2628	44	0.02	2	1161	16	0.63	<5	4	192	<5	0.01	<10	14	62	<10	238	2
120753	2.0	2.11	86	132	<0.5	<5	2.96	3	16	9	106	5.97	<1	0.37	<10	1.04	2224	12	0.01	2	1215	54	1.33	<5	3	106	<5	0.01	<10	12	65	<10	227	2
120754	3.8	1.42	128	102	<0.5	<5	5.17	5	13	16	177	4.34	<1	0.31	<10	0.64	2391	34	0.01	2	1072	178	1.41	<5	3	213	<5	0.01	<10	13	45	<10	316	1
120755	1.9	2.25	25	105	<0.5	<5	2.96	1	23	9	113	5.68	<1	0.31	<10	0.94	1881	8	0.01	4	1127	21	0.99	<5	4	103	<5	0.06	<10	<10	81	<10	153	2
120756	2.1	2.19	22	94	<0.5	<5	4.91	4	19	9	178	4.81	<1	0.25	<10	1.27	1948	8	0.02	3	1047	171	0.46	<5	4	180	<5	0.04	<10	<10	75	<10	466	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3215RJ

Date : Sep-25-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment24

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120757	23.9	2.06	29	97	<0.5	<5	3.53	49	20	8	929	5.11	<1	0.25	<10	1.13	1965	12	0.01	3	1052	9473	1.36	9	4	119	<5	0.01	<10	<10	80	48	4991	1
120758	2.9	2.46	10	77	<0.5	<5	4.90	18	19	9	250	5.16	<1	0.13	<10	1.76	2027	20	0.02	3	990	136	0.51	<5	6	175	<5	0.06	<10	<10	92	17	1684	2
120759	1.7	2.41	<5	95	<0.5	<5	4.48	3	21	7	213	5.06	<1	0.21	<10	1.38	1698	5	0.02	3	1042	45	0.29	<5	5	169	<5	0.06	<10	<10	74	<10	337	3
120760	2.0	2.13	15	136	<0.5	<5	3.58	3	20	8	176	5.16	<1	0.30	<10	1.04	1757	2	0.02	3	1140	27	0.76	<5	4	119	<5	0.06	<10	10	65	<10	344	2
120761	0.6	2.00	<5	90	<0.5	<5	4.41	<1	19	5	58	4.35	<1	0.26	<10	1.16	1586	2	0.02	2	1092	19	0.59	<5	4	133	<5	0.07	<10	<10	63	<10	119	2
120762	0.9	2.10	11	92	<0.5	<5	4.44	2	22	5	75	5.03	<1	0.27	<10	1.11	1826	7	0.02	3	1126	49	0.75	<5	4	142	<5	0.06	<10	<10	59	<10	202	2
120763	1.1	2.13	28	95	<0.5	<5	6.45	1	21	4	77	4.94	<1	0.27	<10	1.11	2330	4	0.01	2	1065	28	0.57	<5	3	319	<5	0.06	<10	11	58	<10	128	2
120764	2.2	2.09	94	105	<0.5	<5	3.60	12	20	10	90	5.52	<1	0.21	<10	1.11	2581	7	0.01	3	1047	257	1.24	<5	4	183	<5	0.04	<10	12	78	12	1232	2
120765	2.5	1.89	41	110	<0.5	<5	3.88	6	19	7	192	4.80	<1	0.31	<10	0.90	2045	2	0.02	2	1072	37	1.01	<5	3	132	<5	0.02	<10	11	51	<10	593	2
120766	2.8	2.27	49	101	<0.5	<5	2.79	5	22	11	182	5.79	<1	0.27	<10	1.13	2130	4	0.01	3	1043	605	0.94	<5	4	91	<5	0.01	<10	12	71	<10	419	2
120767	1.0	2.02	8	124	<0.5	<5	3.27	2	19	6	76	4.77	<1	0.30	<10	0.92	1957	21	0.01	2	1108	39	0.46	<5	3	146	<5	<0.01	<10	11	54	<10	205	1
120768	1.1	2.07	19	105	<0.5	<5	3.51	1	19	8	67	5.06	<1	0.27	<10	0.97	2102	6	0.01	2	1098	43	0.74	<5	3	135	<5	<0.01	<10	12	59	<10	132	1
120769	7.0	2.08	78	95	<0.5	<5	2.59	27	19	8	348	5.84	<1	0.25	<10	1.08	1869	<2	0.01	2	988	126	1.84	<5	3	88	<5	<0.01	<10	13	60	24	2507	2
120770	1.7	2.09	87	89	<0.5	<5	2.20	5	20	8	68	5.86	<1	0.23	<10	1.05	1700	<2	0.01	3	1033	62	1.67	<5	3	88	<5	<0.01	<10	11	69	<10	411	2
120771	1.0	2.03	38	96	<0.5	<5	3.29	1	17	7	47	4.99	<1	0.27	<10	0.96	1599	<2	0.01	2	1079	24	0.74	<5	3	121	<5	<0.01	<10	<10	60	<10	116	2
120772	0.9	1.70	33	91	<0.5	<5	4.93	6	14	12	35	3.86	<1	0.28	<10	0.93	1601	<2	0.01	2	966	35	0.72	<5	2	170	<5	<0.01	<10	<10	35	<10	467	1
120773	0.6	1.88	15	96	<0.5	<5	4.93	<1	17	5	34	3.93	<1	0.27	10	1.15	1546	<2	0.01	2	1055	36	0.48	<5	2	139	<5	0.02	<10	<10	47	<10	66	1
125774	<0.2	0.21	<5	34	<0.5	<5	0.20	<1	1	80	1	0.51	<1	0.19	13	0.01	234	<2	0.04	2	24	25	0.01	<5	<1	6	15	<0.01	<10	<10	1	<10	29	6
125775	3.0	1.41	568	190	<0.5	185	8.15	13	50	75	450	5.62	10	0.16	12	0.35	825	107	0.04	73	807	87	2.40	<5	3	120	<5	0.09	<10	<10	39	36	98	12
125776	1.2	1.95	31	110	<0.5	<5	2.93	<1	26	7	53	4.40	1	0.27	<10	0.99	1531	<2	0.02	3	1401	15	0.65	<5	5	81	<5	<0.01	<10	<10	77	<10	92	1
125777	<0.2	1.14	6	1432	<0.5	<5	2.85	<1	10	51	5	3.49	<1	0.22	32	0.97	864	2	0.04	8	1574	16	0.13	<5	4	102	<5	0.01	<10	<10	44	<10	73	4
125778	1.8	2.29	47	97	<0.5	<5	4.47	1	22	5	53	6.09	<1	0.30	<10	1.18	2094	<2	0.03	2	1514	33	1.06	<5	6	132	<5	<0.01	<10	10	103	<10	142	2
125779	1.6	2.33	79	77	<0.5	<5	5.13	3	22	15	36	6.13	<1	0.25	<10	1.58	2264	<2	0.01	3	1334	30	1.40	<5	4	160	<5	<0.01	<10	14	80	<10	263	2
125780	4.0	1.78	110	109	<0.5	<5	6.88	7	20	10	84	5.56	<1	0.27	<10	0.87	2715	<2	0.01	2	1166	119	1.39	<5	5	323	<5	0.01	<10	16	72	<10	565	2
125781	3.0	2.03	46	61	<0.5	<5	8.57	1	18	26	82	6.11	<1	0.18	<10	0.85	3851	<2	0.02	2	964	26	0.90	<5	5	150	<5	0.04	<10	21	79	<10	97	3
125782	<0.2	0.96	<5	526	<0.5	<5	3.05	<1	8	35	<1	2.12	<1	0.21	12	0.73	497	<2	0.03	4	764	4	0.04	<5	2	94	<5	<0.01	<10	<10	23	<10	45	4
125783	3.4	1.66	113	168	<0.5	<5	6.40	3	20	17	74	4.90	<1	0.35	<10	0.81	2259	<2	0.01	3	1154	63	1.56	<5	5	191	<5	0.01	<10	11	69	<10	138	2
125784	4.0	1.76	81	113	<0.5	<5	6.44	3	28	14	64	5.47	<1	0.31	<10	0.83	2230	<2	0.01	3	1276	73	1.48	<5	5	254	<5	<0.01	<10	14	64	<10	186	2
125785	2.8	1.03	154	107	<0.5	<5	4.76	5	16	31	28	4.34	<1	0.32	<10	0.45	1926	3	<0.01	3	1115	104	2.29	<5	3	180	<5	<0.01	<10	<10	32	<10	130	2
125786	3.5	1.70	191	75	<0.5	<5	4.13	6	26	15	79	5.60	<1	0.27	<10	0.96	2043	<2	<0.01	3	1264	45	1.95	<5	4	156	<5	<0.01	<10	12	59	<10	135	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3215RJ

Date : Sep-25-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment24

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
125787	1.6	2.00	23	71	<0.5	<5	4.43	<1	21	16	39	5.41	<1	0.31	<10	1.03	2058	<2	0.01	2	1255	11	0.81	<5	4	154	<5	<0.01	<10	11	65	<10	88	2
125788	1.6	1.95	41	70	<0.5	<5	4.49	1	19	13	43	5.35	<1	0.26	<10	1.05	2059	<2	0.02	2	1278	23	0.92	<5	4	190	<5	<0.01	<10	12	72	<10	132	2
125789	3.8	1.67	143	79	<0.5	<5	4.67	4	20	19	65	5.89	<1	0.29	<10	0.93	2322	<2	0.01	2	1236	121	2.23	<5	4	197	<5	<0.01	<10	15	54	<10	149	2
125790	3.4	1.64	328	80	<0.5	<5	3.94	8	24	15	56	5.71	<1	0.29	<10	0.79	2108	<2	<0.01	3	1309	19	2.10	<5	3	167	<5	<0.01	<10	13	52	<10	89	2
125791	1.7	1.91	168	146	<0.5	<5	5.26	4	18	16	33	5.13	<1	0.42	<10	0.90	2309	<2	0.01	2	1326	17	1.21	<5	5	195	<5	<0.01	<10	12	62	<10	70	2
125792	<0.2	1.46	9	444	<0.5	<5	4.06	<1	16	48	12	4.54	<1	0.26	33	1.58	934	<2	0.03	11	2365	33	0.20	<5	6	240	<5	<0.01	<10	<10	38	<10	158	3
125793	1.6	1.96	73	124	<0.5	<5	4.28	2	22	12	61	5.68	<1	0.33	<10	1.12	2117	<2	0.02	3	1353	18	0.96	<5	5	229	<5	<0.01	<10	12	74	<10	123	2
125794	2.2	1.74	530	98	<0.5	<5	4.23	13	22	13	60	5.63	<1	0.28	<10	0.85	2099	<2	0.01	3	1348	55	1.64	<5	4	185	<5	<0.01	<10	12	70	<10	144	2
125795	80.9	1.46	146	117	<0.5	<5	4.65	4	21	15	73	5.33	<1	0.31	<10	0.70	2151	<2	<0.01	3	1324	37	1.99	<5	4	208	<5	<0.01	<10	11	55	<10	134	2
125796	2.4	1.09	255	116	<0.5	<5	5.49	7	22	12	78	4.73	<1	0.33	<10	0.52	1894	<2	<0.01	3	1559	32	2.32	<5	3	287	<5	<0.01	<10	<10	39	<10	101	2
125797	2.0	1.31	111	109	<0.5	<5	7.64	3	18	43	52	4.83	<1	0.31	<10	0.67	2238	<2	0.01	3	1140	21	1.78	<5	4	320	<5	<0.01	<10	13	45	<10	83	1
125798	1.2	1.90	30	103	<0.5	<5	5.89	1	24	12	65	5.60	<1	0.27	<10	1.08	2438	<2	0.01	3	1516	31	0.97	<5	5	344	<5	<0.01	<10	14	68	<10	126	2
125799	1.3	1.82	30	138	0.5	5	5.39	1	25	16	78	5.88	<1	0.37	<10	1.22	2296	<2	0.01	3	1590	57	1.03	<5	5	347	<5	<0.01	<10	15	59	<10	155	2
125800	<0.2	0.95	<5	252	<0.5	<5	0.52	<1	8	111	<1	2.27	<1	0.48	<10	0.64	601	<2	0.05	5	723	3	<0.01	<5	2	46	<5	0.11	<10	<10	39	<10	50	1
125801	1.6	1.85	86	106	<0.5	5	2.55	2	29	24	63	6.42	<1	0.30	<10	0.94	1781	3	0.02	4	1303	48	1.45	<5	4	143	<5	<0.01	<10	12	75	<10	155	2
125802	0.9	1.59	57	128	<0.5	<5	2.50	1	18	19	25	5.28	<1	0.35	<10	0.68	1626	12	0.02	3	1409	23	1.10	<5	4	143	<5	<0.01	<10	<10	62	<10	71	2
125803	1.2	1.95	79	116	<0.5	<5	1.77	5	25	25	51	6.30	<1	0.29	<10	0.79	1400	2	0.02	4	1264	32	1.23	<5	4	100	<5	<0.01	<10	<10	83	<10	442	2
125804	1.3	2.17	135	139	<0.5	5	1.22	3	30	16	60	6.76	<1	0.36	<10	0.86	1400	<2	0.02	4	1298	67	1.37	<5	4	63	<5	<0.01	<10	<10	85	<10	122	2
125805	2.6	1.77	150	157	<0.5	5	1.19	5	30	27	56	6.48	<1	0.41	<10	0.63	1039	18	0.01	4	1319	108	2.57	<5	4	59	<5	<0.01	<10	10	63	<10	237	3
125806	<0.2	0.83	5	97	<0.5	<5	2.65	<1	9	33	13	2.54	<1	0.26	11	0.75	578	4	0.03	4	778	11	0.38	<5	3	172	<5	<0.01	<10	<10	17	<10	47	4
125807	3.9	0.97	396	52	<0.5	5	0.77	11	28	37	107	7.25	<1	0.38	<10	0.30	373	<2	0.01	4	1419	79	>5.00	<5	2	36	<5	<0.01	<10	11	29	<10	249	3
125808	3.3	0.64	272	93	<0.5	<5	1.71	8	21	26	78	5.64	<1	0.37	<10	0.27	671	<2	0.01	3	1351	71	4.98	<5	2	82	<5	<0.01	<10	<10	20	<10	243	2
125809	8.6	1.66	1026	67	<0.5	6	2.74	28	31	93	129	8.31	<1	0.58	<10	0.58	1545	2	0.01	7	1882	495	>5.00	8	4	116	<5	<0.01	<10	16	55	<10	382	4
125810	4.7	0.54	438	81	<0.5	5	1.71	12	24	26	90	6.17	<1	0.35	<10	0.12	563	<2	<0.01	3	1274	63	>5.00	<5	2	63	<5	<0.01	<10	<10	16	<10	134	3
125811	5.5	0.39	496	75	<0.5	<5	2.81	14	19	60	64	4.33	<1	0.27	<10	0.08	1008	<2	<0.01	3	850	92	4.43	5	1	91	<5	<0.01	<10	<10	9	<10	229	2
125812	3.1	1.71	183	102	<0.5	<5	1.58	5	29	28	71	6.55	<1	0.32	<10	0.71	1439	<2	<0.01	4	1266	57	2.74	<5	3	67	<5	<0.01	<10	10	68	<10	144	2
125813	3.2	1.81	135	100	<0.5	<5	1.89	3	27	35	76	6.47	<1	0.33	<10	0.74	1551	<2	0.01	4	1338	38	2.31	<5	4	78	<5	<0.01	<10	11	73	<10	97	2
125814	5.0	1.25	176	86	<0.5	<5	3.38	5	32	22	128	5.75	<1	0.28	<10	0.64	1798	<2	<0.01	3	1259	47	2.67	<5	3	145	<5	<0.01	<10	11	52	<10	87	2
125815	3.5	1.30	84	104	<0.5	<5	3.44	3	24	28	61	6.17	<1	0.34	<10	0.69	1990	<2	0.01	5	1237	103	2.11	<5	5	149	<5	<0.01	<10	11	67	<10	230	2
125816	3.9	1.23	143	99	<0.5	<5	2.46	3	25	26	64	5.73	<1	0.33	<10	0.56	1564	6	0.01	4	1223	42	2.44	<5	4	70	<5	<0.01	<10	<10	61	<10	81	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3215RJ

Date : Sep-25-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment24

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
125817	<0.2	0.23	5	49	<0.5	<5	1.50	<1	2	97	2	0.88	<1	0.20	<10	0.06	735	<2	0.05	2	39	19	0.08	<5	1	84	13	<0.01	<10	<10	2	<10	23	5
125818	3.4	1.16	299	114	<0.5	<5	2.56	10	24	20	51	5.46	<1	0.34	<10	0.48	1472	<2	0.01	5	1235	95	2.76	<5	4	100	<5	<0.01	<10	<10	51	<10	375	2
125819	8.4	0.53	1217	133	<0.5	<5	1.46	32	21	110	101	5.02	<1	0.43	<10	0.10	605	3	0.01	7	998	640	4.82	11	2	59	<5	<0.01	<10	<10	18	<10	480	2
125820	4.6	0.59	683	84	<0.5	<5	1.39	19	22	36	50	5.14	<1	0.28	<10	0.20	760	2	<0.01	5	906	89	4.77	5	2	61	<5	<0.01	<10	<10	28	<10	127	2
125821	2.1	1.37	329	135	<0.5	<5	0.75	9	17	18	34	4.07	<1	0.43	<10	0.53	1018	<2	<0.01	4	658	52	1.49	<5	2	24	<5	<0.01	<10	<10	41	<10	201	2
125822	4.1	1.08	350	115	<0.5	<5	1.95	11	16	22	60	4.69	<1	0.42	<10	0.47	1167	3	0.01	3	877	68	3.27	5	2	89	<5	<0.01	<10	<10	27	<10	280	2
125823	4.5	0.52	883	68	<0.5	<5	1.26	24	16	38	37	5.46	<1	0.41	<10	0.08	535	<2	<0.01	4	1071	79	>5.00	13	2	69	<5	<0.01	<10	<10	11	<10	281	2
125824	5.2	0.64	584	59	<0.5	<5	0.69	16	19	41	55	5.62	<1	0.40	<10	0.15	392	2	<0.01	3	926	101	>5.00	10	1	35	<5	<0.01	<10	<10	13	<10	216	3
125825	>200.0	0.65	487	187	<0.5	136	0.58	21	7	20	7506	2.44	5	0.16	<10	0.62	294	459	0.03	4	346	949	1.28	1422	2	75	<5	0.05	<10	<10	22	<10	938	2
125826	6.4	1.10	1100	108	<0.5	<5	0.90	34	17	45	74	5.08	<1	0.36	<10	0.49	966	4	<0.01	5	814	114	3.19	21	2	36	<5	<0.01	<10	<10	30	<10	626	2
125827	5.4	1.08	466	118	<0.5	<5	0.93	12	20	28	105	4.43	<1	0.43	<10	0.41	815	<2	<0.01	4	1256	30	2.79	11	3	39	<5	<0.01	<10	<10	42	<10	58	2
125828	3.1	1.36	182	120	<0.5	<5	3.23	5	17	23	51	4.53	<1	0.37	<10	0.66	1207	<2	<0.01	6	663	28	2.07	<5	2	78	<5	<0.01	<10	<10	47	<10	77	2
125829	2.0	1.92	40	126	<0.5	<5	6.93	1	19	16	58	4.27	<1	0.34	<10	1.18	1957	<2	<0.01	7	1097	19	0.59	<5	4	161	<5	<0.01	<10	<10	75	<10	49	1
125830	2.5	1.25	98	125	<0.5	<5	2.95	3	12	21	48	3.52	<1	0.34	<10	0.51	1552	2	<0.01	4	970	73	1.02	<5	2	110	<5	<0.01	<10	<10	37	<10	82	1
125831	3.4	1.51	88	148	<0.5	<5	1.58	3	15	19	59	4.07	<1	0.40	<10	0.61	1362	3	<0.01	5	1071	43	1.14	<5	3	67	<5	<0.01	<10	<10	48	<10	146	2
125832	8.1	1.26	468	117	<0.5	<5	2.45	13	18	42	85	4.80	<1	0.41	<10	0.49	1261	2	<0.01	5	907	79	2.73	6	3	79	<5	<0.01	<10	<10	41	<10	182	2
125833	8.8	1.02	556	61	<0.5	5	0.69	16	24	36	217	6.48	<1	0.46	<10	0.34	545	<2	<0.01	4	1197	71	>5.00	9	3	31	<5	<0.01	<10	<10	27	<10	210	3
125914	0.2	0.31	5	41	<0.5	<5	0.45	<1	1	119	3	0.63	<1	0.26	13	0.01	364	<2	0.07	2	31	21	0.05	<5	1	10	13	<0.01	<10	<10	1	<10	18	7
125915	1.3	1.68	88	283	0.7	<5	2.16	2	27	31	38	5.77	<1	0.37	12	0.88	1207	2	0.02	5	1316	25	1.29	<5	4	67	<5	<0.01	<10	<10	59	<10	116	4
125916	1.6	2.22	53	266	0.5	<5	4.89	1	18	16	51	5.84	<1	0.32	<10	1.15	1933	<2	0.02	2	1388	21	1.28	<5	5	181	<5	<0.01	<10	11	86	<10	92	2
125857	6.6	1.32	438	76	<0.5	5	3.16	11	23	25	45	6.68	<1	0.39	<10	0.54	1550	<2	0.01	3	1389	47	>5.00	8	4	103	<5	<0.01	<10	13	49	<10	84	3
125866	4.2	0.60	406	80	<0.5	<5	0.95	11	19	63	24	4.97	<1	0.37	<10	0.15	323	2	0.01	6	733	58	4.88	5	1	57	<5	<0.01	<10	<10	14	<10	75	2
125870	>200.0	1.18	242	99	<0.5	<5	1.65	8	23	25	222	5.39	<1	0.37	<10	0.44	815	<2	<0.01	4	1136	176	3.72	85	2	70	<5	<0.01	<10	<10	30	<10	321	2
125898	6.5	0.37	269	84	<0.5	<5	7.78	11	9	70	28	2.91	<1	0.23	<10	0.16	2076	4	<0.01	3	512	189	2.78	6	1	290	<5	<0.01	<10	10	11	<10	597	1
125945	4.1	1.68	86	131	<0.5	<5	7.77	2	17	27	27	5.39	<1	0.31	<10	1.23	2154	<2	0.01	2	992	18	3.33	<5	5	268	<5	<0.01	<10	15	44	<10	59	2
125946	0.9	1.55	80	143	<0.5	<5	5.71	2	16	37	27	5.00	<1	0.39	<10	1.12	1834	<2	0.01	2	1158	26	3.19	<5	5	188	<5	0.01	<10	12	51	<10	62	2
125947	0.9	1.16	90	59	<0.5	<5	3.66	2	20	40	47	4.83	<1	0.37	<10	0.60	1236	<2	0.01	2	1052	28	4.43	<5	5	114	<5	0.01	<10	<10	44	<10	68	2
125948	0.5	1.75	39	107	<0.5	<5	5.53	1	16	32	24	4.42	<1	0.41	<10	0.88	1952	<2	0.04	2	1011	20	2.36	<5	8	120	<5	0.06	<10	<10	75	<10	86	3
125949	0.5	2.01	19	311	<0.5	<5	3.90	<1	15	33	42	3.27	<1	0.43	<10	1.04	1429	<2	0.06	2	1101	11	1.10	<5	9	93	<5	0.06	<10	<10	100	<10	79	2
125950	<0.2	0.88	<5	244	<0.5	<5	0.43	<1	8	114	3	1.91	<1	0.42	<10	0.55	551	<2	0.05	5	666	3	<0.01	<5	2	41	<5	0.11	<10	<10	38	<10	51	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3215RJ

Date : Sep-25-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment24

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139478	1.0	0.39	46	64	<0.5	<5	0.91	1	11	81	37	4.96	2	0.17	<10	0.09	196	<2	0.01	5	894	45	>5.00	6	1	40	<5	<0.01	<10	<10	8	<10	92	2
139479	0.6	0.49	37	74	<0.5	<5	0.66	1	10	80	19	3.86	<1	0.17	<10	0.15	173	<2	0.01	4	938	16	3.99	<5	1	30	<5	<0.01	<10	<10	11	<10	52	2
139480	0.6	0.51	32	88	<0.5	<5	0.52	1	9	87	20	3.33	1	0.17	<10	0.18	171	<2	0.01	5	850	22	3.02	<5	1	23	<5	<0.01	<10	<10	11	<10	68	2
139481	0.3	0.43	20	89	<0.5	<5	0.56	1	7	132	7	2.73	1	0.16	<10	0.13	164	<2	0.01	4	600	79	2.39	<5	1	23	<5	<0.01	<10	<10	10	<10	78	1
139482	0.5	0.23	49	71	<0.5	<5	0.50	2	6	134	16	2.44	<1	0.12	<10	0.03	96	<2	0.01	5	522	72	2.41	<5	1	23	<5	<0.01	<10	<10	4	<10	137	1
139483	0.6	0.39	44	92	<0.5	<5	0.30	2	7	111	7	2.60	1	0.15	<10	0.13	133	<2	0.01	4	542	120	2.43	<5	1	14	<5	<0.01	<10	<10	8	<10	247	1
139484	0.6	0.93	35	105	<0.5	<5	0.32	<1	10	66	15	3.62	<1	0.18	<10	0.48	291	<2	0.02	5	1093	10	2.41	<5	2	13	<5	<0.01	<10	<10	20	<10	49	2
139485	0.8	0.83	41	98	<0.5	<5	0.35	1	10	71	11	3.96	1	0.17	<10	0.39	275	<2	0.02	4	899	11	3.03	<5	1	18	<5	<0.01	<10	<10	20	<10	43	2
139486	0.8	1.03	33	99	<0.5	<5	0.53	<1	9	78	54	4.19	<1	0.15	<10	0.48	411	<2	0.01	5	1083	11	2.45	<5	2	22	<5	<0.01	<10	<10	22	<10	55	2
139487	0.9	0.48	36	85	<0.5	<5	0.91	3	7	108	36	4.09	4	0.18	<10	0.12	206	<2	0.01	3	504	41	3.94	17	1	40	<5	<0.01	22	<10	11	<10	380	2
139488	1.2	0.27	53	80	<0.5	<5	0.65	1	6	157	16	3.81	5	0.14	<10	0.04	120	<2	0.01	5	379	15	4.02	23	1	24	<5	<0.01	23	<10	16	<10	27	2
139489	0.7	1.27	45	161	<0.5	<5	0.22	1	7	62	13	3.61	2	0.20	<10	0.57	347	<2	0.02	3	1121	9	1.13	<5	2	10	<5	<0.01	<10	<10	28	<10	53	2
139520	3.0	1.23	96	207	<0.5	<5	2.91	14	18	65	224	4.23	<1	0.24	<10	0.60	2241	24	<0.01	2	799	343	1.42	<5	3	66	<5	<0.01	<10	10	43	12	1279	1
139521	4.2	0.99	188	143	<0.5	<5	4.59	16	14	62	226	4.80	<1	0.22	<10	0.47	2801	3	<0.01	1	858	728	1.29	<5	3	96	<5	<0.01	<10	16	38	12	1255	1
139522	7.0	1.06	164	114	<0.5	<5	1.91	68	16	82	322	6.13	1	0.22	<10	0.51	1778	<2	0.01	2	831	2255	3.34	<5	2	49	<5	<0.01	<10	13	29	73	7424	2
139523	4.6	0.94	233	222	<0.5	<5	0.11	6	8	80	205	5.43	<1	0.24	<10	0.46	681	44	<0.01	1	939	1282	1.05	<5	2	3	<5	<0.01	<10	<10	31	<10	314	2
139524	5.0	0.74	322	100	<0.5	<5	0.12	7	13	71	179	6.48	<1	0.21	<10	0.34	764	24	<0.01	1	997	801	2.83	<5	2	3	<5	<0.01	<10	11	22	<10	252	3
139525	4.5	0.61	283	155	<0.5	<5	0.22	8	9	93	159	5.93	<1	0.18	<10	0.27	930	39	<0.01	1	906	1283	2.10	<5	2	6	<5	<0.01	<10	10	22	<10	473	2
139526	3.8	0.43	258	125	<0.5	<5	0.82	10	10	117	193	5.58	<1	0.23	<10	0.22	1278	23	0.01	3	1005	587	2.96	<5	2	27	<5	<0.01	<10	10	12	<10	837	2
139527	2.6	0.65	216	174	<0.5	<5	0.39	6	10	92	110	5.28	<1	0.16	<10	0.36	1461	52	0.01	2	874	547	1.83	<5	2	11	<5	<0.01	<10	10	23	<10	299	2
139528	1.9	0.61	144	270	<0.5	<5	0.09	6	13	123	126	4.68	<1	0.22	<10	0.23	2725	94	0.01	3	1025	70	0.86	<5	3	4	<5	<0.01	<10	12	18	<10	255	2
139529	2.4	0.99	62	137	<0.5	<5	0.52	5	14	65	239	4.50	<1	0.23	<10	0.55	1851	75	0.01	1	1073	67	0.80	<5	3	12	<5	<0.01	<10	<10	30	<10	480	1
SD08-20	<0.2	0.68	11	144	<0.5	<5	0.01	<1	4	42	25	4.06	<1	0.17	33	0.21	352	7	0.02	3	926	26	0.43	<5	3	2	6	<0.01	<10	<10	11	<10	106	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3283-RA1

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-30-08

We hereby certify the following assay of 22 core samples submitted Sep-11-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120751	0.64	0.67	3.7
120752	0.17		1.7
120753	0.01		1.1
120754	0.62		0.8
120755	0.71		2.1
120756	0.07		1.4
120757	0.47		1.8
120758	16.87		13.7
120759	0.44		3.3
120760	0.14	0.10	1.8
120761	0.36		1.8
120762	0.08		0.9
120763	0.70		1.5
120764	1.27		1.6
120765	0.34		3.5
120766	0.02		0.5
120767	0.02		0.9
120768	<0.01		0.7
120769	0.01		0.5
120770	<0.01	0.01	0.6
120771	0.01		0.8
120772	0.01		1.0
*0211	2.17		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3283-RA2

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-30-08

We hereby certify the following assay of 22 core samples submitted Sep-11-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120773	0.01	0.03	0.8
120774	0.02		0.9
120775	<0.01		<0.1
120776	0.01		0.7
120777	0.02		1.0
120778	0.02		1.2
120779	1.51		13.7
120780	0.02		1.0
120781	0.05		1.1
120782	0.02	0.03	0.5
120783	0.03		2.0
120784	0.02		1.0
120785	0.03		0.9
120786	0.02		0.7
120787	0.02		0.8
120788	0.02		1.0
120789	0.11		0.7
120790	0.43		3.3
120791	0.02		0.6
120792	0.02	0.01	<0.1
120793	0.01		0.3
120794	0.05		0.4
*0211	2.26		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3283-RA3

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-30-08

We hereby certify the following assay of 22 core samples submitted Sep-11-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120795	<0.01	0.01	<0.1
120796	<0.01		0.3
120797	<0.01		0.7
120798	0.01		1.2
120799	0.28		5.6
120800	6.38		3.6
120801	0.06		2.8
120802	0.01		1.8
120803	0.01		1.3
120804	<0.01	<0.01	<0.1
120805	0.01		0.7
120806	<0.01		1.6
120807	<0.01		0.5
120808	0.30		1.3
120809	0.16		2.9
120810	0.07		1.8
120811	0.02		1.0
120812	<0.01		1.6
120813	0.03		1.6
120814	0.07	0.10	0.9
120815	0.03		1.7
120816	0.11		2.2
*0211	2.09		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3283-RA4

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-30-08

We hereby certify the following assay of 22 core samples submitted Sep-11-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag-Rerun g/tonne
120817	5.75	5.75	5.1	3.9
120818	0.22		2.0	2.1
120819	0.27		5.2	5.3
120820	0.23		1.0	2.9
120821	0.14		2.6	2.3
120822	0.11		1.9	1.7
120823	0.10		2.5	2.5
120824	0.25		3.0	2.9
120825	1.88		3.8	160
120826	0.29	0.29	27.2	28.5
120827	0.11		1.2	1.1
120828	0.02		1.1	1.1
120829	12.77		22.7	16.2
120830	0.03		0.8	0.7
120831	0.03		0.9	1.1
120832	0.03		1.1	1.1
120833	0.02		1.2	1.0
120834	0.04		0.5	7.6
120835	0.05		3.3	3.2
120836	0.03	0.02	1.4	1.2
120837	0.05		2.1	2.1
120838	0.07		1.6	1.7
*0211	2.17			
*BLANK	<0.01			

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3283-RA5

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-30-08

We hereby certify the following assay of 22 core samples submitted Sep-11-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120839	0.01	0.02	2.0
120840	0.96		18.7
120841	0.05		2.4
120842	<0.01		2.5
120843	0.03		1.9
120844	<0.01		1.4
120845	0.02		1.7
120846	0.22		7.0
120847	0.21		8.3
120848	0.04	0.05	3.9
120849	0.06		4.2
120850	0.01		<0.1
120851	0.02		2.2
120852	1.82		6.1
120853	0.01		1.1
120854	0.10		3.3
120855	0.02		1.3
120856	0.04		0.6
120857	0.27		1.5
120858	0.31	0.29	15.4
120859	0.09		2.5
120860	0.94		1.6
*0211	2.10		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3283-RA6

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-30-08

We hereby certify the following assay of 22 core samples submitted Sep-11-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
125834	0.47	0.32	5.3
125835	5.32		8.1
125836	1.39		5.0
125837	0.25		4.1
125838	0.12		1.5
125839	0.07		2.4
125840	0.04		0.8
125841	0.03		2.7
125842	0.04		1.1
125843	<0.01	<0.01	<0.1
125844	0.01		1.5
125845	0.02		1.8
125846	0.02		2.1
125847	0.08		6.0
125848	1.09		3.1
125849	0.02		<0.1
125850	0.01		<0.1
125851	0.15		2.8
125852	0.24		3.1
125853	0.24	0.29	3.8
125854	0.25		3.3
125855	0.20		7.1
*0211	2.21		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3283-RA7

Company: **Ascot Resources Ltd.**
 Project: **Dilworth**
 Attn: **Sue Deane**

Sep-30-08

We hereby certify the following assay of 22 core samples submitted Sep-11-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
125856	0.22	0.21	3.5	
125858	0.14		3.4	
125859	0.13		2.3	
125860	0.15		2.5	
125861	<0.01		<0.1	
125862	0.02		1.5	
125863	0.06		2.3	
125864	0.13		3.0	
125865	0.07		1.7	
125867	0.06	0.08	2.1	
125868	0.12		3.6	
125869	0.10		1.9	
125871	0.06		1.7	
125872	0.01		0.8	
125873	0.02		1.2	
125874	0.09		4.9	
125875	0.19		>200	763.2
125876	0.07		3.7	
125877	0.53		36.8	
125878	0.24	0.24	3.0	
125879	<0.01		1.6	
125880	0.05		2.5	
*0211	2.14			
*CCu-1c				130.6
*BLANK	<0.01			<0.1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3283-RA8

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-30-08

We hereby certify the following assay of 22 core samples submitted Sep-11-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
125881	0.03	0.04	1.9
125882	0.34		3.1
125883	0.04		1.8
125884	0.02		1.9
125885	0.22		2.5
125886	0.20		6.9
125887	0.21		4.2
125888	0.06		1.9
125889	0.03		1.2
125890	0.06	0.07	1.5
125891	0.06		1.2
125892	0.10		1.0
125893	0.11		1.9
125894	0.24		6.4
125895	0.12		2.2
125896	0.08		2.5
125897	0.15		2.7
125899	0.07		1.8
125900	<0.01		<0.1
125901	0.03	0.04	1.3
125902	0.24		2.6
125903	0.11		2.5
*0211	2.16		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3283-RA9

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-30-08

We hereby certify the following assay of 22 core samples submitted Sep-11-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
125904	0.19	0.24	2.8
125905	0.06		2.9
125906	0.02		1.2
125907	0.07		0.8
125908	0.13		1.3
125909	0.01		0.7
125910	0.02		0.9
125911	0.01		1.1
125912	0.01		0.6
125913	0.03	0.08	0.9
125917	0.03		1.8
125918	0.11		2.4
125919	0.26		2.0
125920	0.02		<0.1
125921	0.03		1.3
125922	0.04		1.2
125923	0.06		2.2
125924	0.55		2.8
125925	0.43		0.6
125926	0.16	0.18	2.4
125927	0.15		<0.1
125928	0.02		0.7
*0211	2.18		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3283-RA10

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-30-08

We hereby certify the following assay of 22 core samples submitted Sep-11-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
125929	0.91	0.91	3.9
125930	0.02		1.8
125931	0.03		1.4
125932	0.08		2.6
125933	0.31		5.0
125934	0.11		2.3
125935	0.18		2.6
125936	0.26		4.5
125937	0.22		3.8
125938	0.05	0.07	2.2
125939	0.48		17.5
125940	0.16		12.9
125941	0.30		17.8
125942	0.10		10.1
125943	0.15		2.3
125944	0.04		0.8
125951	<0.01		<0.1
125952	0.04		1.4
125953	0.20		1.4
125954	0.05	0.08	1.5
125955	<0.01		0.1
125956	0.08		2.8
*0211	2.12		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3283-RA11

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-30-08

We hereby certify the following assay of 22 core samples submitted Sep-11-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
125957	0.04	0.04	2.8
125958	0.05		2.2
125959	0.07		2.9
125960	0.06		2.4
125961	0.05		2.7
125962	0.03		1.3
125963	0.03		1.2
125964	0.04		1.0
125965	0.07		1.1
125966	0.07	0.06	1.8
125967	0.02		1.0
125968	0.03		1.5
125969	0.17		2.4
125970	0.06		1.6
125971	0.05		1.7
125972	0.09		3.1
125973	0.06		1.9
125974	0.10		1.5
125975	1.83		162
139256	0.01	0.02	0.5
139257	<0.01		0.3
139258	<0.01		0.1
*0211	2.14		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3283-RA12

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-30-08

We hereby certify the following assay of 22 core samples submitted Sep-11-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
139259	0.02	0.03	0.5
139260	0.02		0.6
139261	0.05		2.1
139262	0.06		3.0
139263	0.05		1.9
139264	0.02		2.4
139265	0.02		1.3
139266	0.01		1.6
139267	0.02		2.5
139490	0.05	0.05	1.0
139491	0.02		0.6
139492	0.08		0.5
139493	0.07		0.3
139494	0.03		0.5
139495	0.05		0.6
139496	0.09		0.8
139497	0.05		0.9
139498	0.02		0.5
139499	0.02		0.4
139500	0.02	0.03	0.4
139530	0.07		0.5
139531	0.03		0.5
*0211	2.13		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3283-RA13

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-30-08

We *hereby certify* the following assay of 10 core samples submitted Sep-11-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
139532	0.02	0.03	0.5
139533	0.02		0.3
139534	0.01		0.4
139535	<0.01		0.2
139536	0.01		0.3
139537	0.01		1.1
139538	0.01		<0.1
139539	0.02		0.3
139540	0.02		1.1
SD08-21	0.01	0.01	<0.1
*0211	2.18		
*BLANK	<0.01		

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3283RJ

Date : Sep-30-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120751	3.7	1.21	84	111	<0.5	<5	2.45	5	13	10	42	3.89	<1	0.28	<10	0.46	1730	<2	0.01	3	1164	62	1.87	<5	2	51	<5	<0.01	<10	<10	16	<10	589	1
120752	1.7	1.62	143	141	<0.5	<5	1.98	3	16	11	36	4.71	<1	0.31	10	0.65	1836	<2	0.02	3	1202	12	1.73	<5	2	43	<5	<0.01	<10	<10	24	<10	103	2
120753	1.1	1.51	37	138	<0.5	<5	3.77	1	16	5	17	4.63	<1	0.29	<10	0.65	1993	<2	0.02	3	1243	9	1.94	<5	2	88	<5	<0.01	<10	11	25	<10	90	2
120754	0.8	1.86	41	133	<0.5	<5	2.97	1	15	7	30	4.84	<1	0.27	<10	0.91	2144	<2	0.02	3	1215	6	1.22	<5	2	65	<5	<0.01	<10	10	35	<10	98	2
120755	2.1	1.38	166	175	<0.5	<5	3.94	6	12	7	25	4.22	<1	0.29	<10	0.55	2202	<2	0.02	2	1111	122	1.57	<5	2	90	<5	<0.01	<10	11	24	<10	459	1
120756	1.4	1.86	46	135	<0.5	<5	2.57	1	15	7	28	4.83	<1	0.25	<10	0.90	1880	<2	0.02	3	1162	16	1.19	<5	2	61	<5	<0.01	<10	<10	39	<10	114	2
120757	1.8	0.68	264	159	<0.5	<5	1.87	7	13	22	13	4.08	<1	0.30	<10	0.26	1004	<2	0.02	3	844	37	3.31	<5	2	61	<5	<0.01	<10	<10	18	<10	201	2
120758	13.7	0.74	113	79	<0.5	<5	1.92	2	18	20	27	4.69	<1	0.32	<10	0.26	975	3	0.01	4	1075	20	4.61	<5	2	59	<5	<0.01	<10	<10	24	<10	54	2
120759	3.3	1.31	147	88	<0.5	<5	3.95	4	23	10	100	5.50	<1	0.33	<10	0.69	1569	<2	0.01	3	1101	56	3.98	<5	3	123	<5	<0.01	<10	12	43	<10	165	2
120760	1.8	2.87	51	156	<0.5	<5	4.60	<1	25	9	71	7.38	<1	0.36	<10	2.21	2475	<2	0.01	4	1386	17	1.90	<5	4	111	<5	0.01	<10	15	89	<10	93	2
120761	1.8	1.33	79	119	<0.5	<5	3.47	2	25	19	46	4.68	<1	0.27	<10	0.80	1774	<2	0.01	10	1212	23	2.92	<5	3	118	<5	0.03	<10	12	44	<10	121	2
120762	0.9	1.73	78	125	<0.5	<5	4.15	2	19	3	31	4.39	<1	0.25	<10	0.99	1739	<2	0.01	3	1132	8	0.86	<5	3	104	<5	<0.01	<10	<10	49	<10	62	2
120763	1.5	1.83	197	138	<0.5	<5	4.12	7	20	4	47	4.68	<1	0.26	<10	0.98	1738	<2	0.01	3	1226	43	0.91	<5	3	96	<5	<0.01	<10	<10	53	<10	389	2
120764	1.6	1.89	72	176	<0.5	<5	5.33	5	21	7	47	5.39	<1	0.31	<10	0.98	1890	<2	0.01	3	1247	49	1.99	<5	3	141	<5	0.02	<10	11	52	<10	511	2
120765	3.5	2.31	44	133	<0.5	<5	4.56	2	24	5	67	5.74	<1	0.25	<10	1.27	2265	<2	0.02	3	1296	134	0.98	<5	4	126	<5	0.01	<10	11	72	<10	197	2
120766	0.5	1.96	23	156	<0.5	<5	3.86	<1	26	5	47	5.87	<1	0.28	<10	1.14	1634	<2	0.02	4	1421	12	2.14	<5	4	132	<5	<0.01	<10	12	67	<10	96	2
120767	0.9	2.10	30	191	<0.5	<5	5.94	<1	24	4	59	6.00	<1	0.32	10	1.08	1961	<2	0.01	4	1438	41	1.88	<5	4	175	<5	0.02	<10	12	66	<10	77	2
120768	0.7	2.18	8	208	<0.5	<5	5.53	1	22	5	54	5.73	<1	0.26	11	1.04	2235	<2	0.02	4	1398	26	0.81	<5	4	151	<5	<0.01	<10	11	75	<10	202	2
120769	0.5	2.27	<5	144	<0.5	<5	4.63	<1	24	4	46	6.02	<1	0.26	<10	1.04	2066	<2	0.02	4	1412	8	0.85	<5	4	128	<5	0.01	<10	11	82	<10	86	2
120770	0.6	2.37	14	141	<0.5	<5	5.28	<1	26	7	46	6.29	<1	0.29	<10	1.32	2220	<2	0.02	4	1446	11	1.40	<5	4	153	<5	0.01	<10	13	77	<10	85	2
120771	0.8	2.43	22	141	<0.5	<5	4.57	1	25	7	53	6.18	<1	0.27	<10	1.32	2132	<2	0.02	4	1498	30	1.12	<5	4	120	<5	0.01	<10	11	80	<10	143	2
120772	1.0	2.49	23	154	<0.5	<5	5.53	1	26	8	60	6.61	<1	0.29	<10	1.36	2316	<2	0.02	5	1585	43	1.24	<5	4	138	<5	<0.01	<10	13	88	<10	129	2
120773	0.8	1.82	28	102	<0.5	<5	7.23	1	21	9	36	5.48	<1	0.21	<10	1.05	2460	2	0.01	4	1309	16	1.68	<5	3	166	<5	<0.01	<10	14	66	<10	95	2
120774	0.9	1.47	50	185	<0.5	<5	7.01	2	20	15	55	5.71	<1	0.32	<10	0.75	2044	<2	0.01	4	1429	25	2.47	<5	4	273	<5	<0.01	<10	11	37	<10	149	2
120775	<0.2	1.13	<5	308	<0.5	<5	0.67	<1	11	96	1	2.81	<1	0.60	<10	0.80	761	<2	0.06	7	916	5	0.02	<5	3	51	5	0.13	<10	<10	50	<10	66	2
120776	0.7	2.16	33	177	<0.5	<5	5.70	1	28	11	52	6.83	<1	0.31	<10	1.37	1950	<2	0.02	4	1552	19	2.25	<5	5	200	<5	<0.01	<10	15	69	<10	103	3
120777	1.0	2.12	48	195	<0.5	<5	5.70	1	27	10	48	6.23	<1	0.35	<10	1.42	2147	<2	0.01	3	1620	44	2.18	<5	5	147	<5	<0.01	<10	12	77	<10	77	2
120778	1.2	1.71	62	163	<0.5	<5	6.20	1	26	7	43	6.35	<1	0.32	<10	1.51	2393	<2	0.01	3	1553	88	2.96	<5	6	143	<5	<0.01	<10	15	57	<10	120	2
120779	13.7	0.89	147	137	<0.5	<5	>15.00	41	15	21	113	5.03	1	0.21	<10	0.83	4584	<2	0.01	2	870	2364	3.18	<5	4	378	<5	<0.01	<10	27	29	49	4935	1
120780	1.0	2.23	34	141	<0.5	5	5.07	<1	28	8	59	6.99	<1	0.27	<10	1.72	2264	<2	0.02	4	1483	23	2.35	<5	5	122	<5	<0.01	<10	14	81	<10	104	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3283RJ

Date : Sep-30-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120781	1.1	1.83	56	136	<0.5	<5	4.42	1	26	13	28	6.86	<1	0.29	<10	1.24	2028	<2	0.01	4	1579	28	3.34	<5	4	136	<5	<0.01	<10	14	66	<10	80	3
120782	0.5	1.70	41	117	<0.5	<5	4.52	2	19	8	37	4.93	1	0.26	<10	1.05	1901	<2	0.01	2	1334	4	1.73	10	3	120	<5	<0.01	<10	<10	62	<10	52	4
120783	2.0	1.69	55	137	<0.5	<5	4.78	1	27	14	55	6.46	<1	0.28	<10	1.12	1895	<2	0.01	4	1542	122	3.49	<5	4	133	<5	<0.01	<10	14	53	<10	124	3
120784	1.0	2.31	49	141	<0.5	<5	6.60	1	27	7	51	7.36	<1	0.32	<10	1.51	2499	<2	0.02	5	1599	16	2.21	<5	4	152	<5	<0.01	<10	17	67	<10	97	2
120785	0.9	1.64	63	153	<0.5	5	5.91	1	30	10	36	7.53	<1	0.38	<10	1.15	2273	<2	0.01	5	1872	23	4.95	<5	4	175	<5	<0.01	<10	18	54	<10	105	3
120786	0.7	2.33	42	138	<0.5	5	6.71	1	28	10	51	7.54	<1	0.32	<10	1.58	2541	<2	0.03	4	1701	18	2.77	<5	6	191	<5	<0.01	<10	17	84	<10	98	3
120787	0.8	2.59	38	149	<0.5	5	4.41	1	32	8	60	7.50	<1	0.24	10	1.43	2160	<2	0.02	5	1664	18	1.08	<5	6	147	<5	<0.01	<10	13	99	<10	111	3
120788	1.0	2.04	27	128	<0.5	<5	7.18	<1	23	7	53	6.00	<1	0.31	<10	1.22	2253	<2	0.02	4	1475	14	1.23	<5	5	145	<5	<0.01	<10	12	67	<10	82	2
120789	0.7	0.40	73	168	<0.5	<5	12.31	3	14	94	13	4.58	<1	0.23	<10	0.71	2598	<2	0.01	4	972	18	2.28	<5	3	625	<5	<0.01	<10	18	14	<10	289	1
120790	3.3	0.49	128	182	<0.5	<5	0.79	3	18	19	33	4.24	<1	0.37	<10	0.16	506	<2	0.01	4	1434	86	1.97	<5	3	17	<5	<0.01	<10	<10	17	<10	207	2
120791	0.6	1.21	30	155	<0.5	<5	5.11	1	23	9	47	5.96	<1	0.27	<10	0.84	1840	<2	0.01	3	1353	10	0.44	<5	5	93	<5	<0.01	<10	12	33	<10	107	2
120792	<0.2	2.20	12	107	<0.5	<5	4.08	2	22	7	35	5.86	<1	0.30	<10	1.27	1417	<2	0.02	2	1524	4	0.30	7	4	115	<5	<0.01	<10	<10	62	<10	76	4
120793	0.3	2.46	13	125	<0.5	<5	4.66	<1	25	8	49	6.39	<1	0.34	<10	1.50	1570	<2	0.02	4	1455	5	0.37	<5	5	131	<5	<0.01	<10	12	63	<10	94	3
120794	0.4	2.92	14	79	<0.5	<5	4.91	<1	32	6	56	7.25	<1	0.17	<10	1.99	1781	<2	0.02	4	1355	4	0.89	<5	7	181	<5	0.01	<10	12	129	<10	95	3
120795	<0.2	2.60	15	104	<0.5	<5	6.93	2	26	8	36	6.25	2	0.25	11	1.63	2105	<2	0.03	6	1841	<2	0.69	<5	6	253	<5	0.01	<10	<10	118	<10	78	4
120796	0.3	2.51	11	114	<0.5	<5	4.02	<1	24	5	48	6.07	<1	0.30	<10	1.48	1428	<2	0.02	4	1541	8	0.85	<5	6	132	<5	0.01	<10	<10	90	<10	78	2
120797	0.7	2.35	17	119	<0.5	<5	5.47	<1	22	4	44	5.45	<1	0.27	<10	1.31	2309	<2	0.02	3	1430	8	0.84	<5	4	171	<5	0.02	<10	13	72	<10	98	2
120798	1.2	2.08	59	172	<0.5	<5	5.50	2	20	4	39	5.34	<1	0.32	<10	1.13	2389	<2	0.01	3	1344	26	1.69	<5	3	153	<5	0.01	<10	13	59	<10	167	2
120799	5.6	1.06	244	146	<0.5	<5	>15.00	17	12	9	64	4.94	<1	0.22	<10	0.58	4390	<2	0.01	2	679	441	3.20	5	3	384	<5	<0.01	<10	27	26	13	1349	1
120800	3.6	1.60	701	165	<0.5	201	9.27	17	58	78	534	6.51	10	0.20	14	0.41	969	131	0.04	87	966	103	2.75	<5	4	134	<5	0.12	<10	<10	47	49	109	15
120801	2.8	1.75	140	129	<0.5	<5	10.20	3	22	7	36	5.56	<1	0.30	10	0.96	3650	<2	0.01	4	1172	20	2.87	<5	3	260	<5	0.01	<10	20	50	<10	58	1
120802	1.8	2.38	67	126	<0.5	<5	7.01	1	26	3	69	6.22	<1	0.29	<10	1.20	2519	<2	0.02	4	1339	19	1.60	<5	4	219	<5	0.01	<10	16	87	<10	93	2
120803	1.3	2.47	43	145	<0.5	<5	4.74	1	29	4	72	6.25	<1	0.35	<10	1.24	2050	<2	0.02	5	1269	11	1.43	<5	4	158	<5	0.02	<10	13	83	<10	104	2
120804	<0.2	2.64	34	167	<0.5	<5	6.48	2	27	3	58	6.49	<1	0.39	<10	1.20	2173	<2	0.03	2	1485	4	0.80	7	5	196	<5	0.01	<10	<10	90	<10	109	4
120805	0.7	1.46	26	172	<0.5	<5	5.45	1	29	3	69	5.71	<1	0.40	<10	1.13	1961	<2	0.02	5	1451	37	0.47	<5	8	207	<5	<0.01	<10	11	47	<10	117	2
120806	1.6	1.36	45	168	<0.5	6	5.57	1	38	4	181	7.87	<1	0.40	<10	1.39	2390	<2	0.04	8	1468	47	0.73	<5	9	189	<5	<0.01	<10	20	53	<10	242	3
120807	0.5	0.90	29	130	<0.5	<5	6.13	<1	20	34	24	4.79	<1	0.29	<10	1.00	1990	<2	0.02	3	1106	38	0.43	<5	5	295	<5	<0.01	<10	12	28	<10	66	1
120808	1.3	1.62	40	124	<0.5	<5	2.19	1	18	6	8	4.89	<1	0.31	14	0.65	1953	<2	0.01	3	1426	19	2.17	<5	2	46	<5	<0.01	<10	<10	22	<10	104	2
120809	2.9	1.32	101	173	<0.5	<5	1.42	2	19	16	24	4.64	<1	0.40	11	0.45	1389	<2	0.01	4	1380	23	2.94	<5	2	34	<5	<0.01	<10	<10	20	<10	110	2
120810	1.8	1.61	33	168	<0.5	<5	1.92	1	17	8	31	4.91	<1	0.39	12	0.61	1725	<2	0.02	3	1523	14	2.50	<5	3	57	<5	<0.01	<10	<10	27	<10	118	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3283RJ**

Date : Sep-30-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120811	1.0	1.69	38	150	<0.5	<5	2.69	1	17	9	12	4.18	<1	0.36	11	0.69	1929	<2	0.02	4	1480	8	1.33	<5	3	84	<5	<0.01	<10	<10	29	<10	89	1
120812	1.6	1.58	89	156	<0.5	<5	3.82	2	18	13	41	4.48	<1	0.32	10	0.67	2503	<2	0.03	4	1237	9	1.85	<5	3	104	<5	<0.01	<10	10	30	<10	94	2
120813	1.6	1.72	68	158	<0.5	<5	2.94	1	16	14	40	4.62	<1	0.32	11	0.72	2216	<2	0.02	6	1359	9	1.51	<5	3	73	<5	<0.01	<10	<10	32	<10	97	2
120814	0.9	1.76	70	186	<0.5	<5	1.49	1	17	6	27	4.64	<1	0.34	10	0.70	1605	<2	0.01	3	1298	8	1.30	<5	2	43	<5	<0.01	<10	<10	30	<10	106	2
120815	1.7	1.47	712	192	<0.5	<5	3.46	17	14	6	4	4.05	<1	0.28	<10	0.50	2325	<2	0.01	2	1024	10	1.51	<5	2	73	<5	<0.01	<10	10	27	<10	66	1
120816	2.2	1.17	165	152	<0.5	<5	1.62	4	12	10	5	4.09	<1	0.22	<10	0.40	1283	<2	0.02	2	810	14	2.01	5	2	44	<5	<0.01	<10	<10	23	<10	62	2
120817	5.1	0.86	237	176	<0.5	<5	1.69	7	14	29	16	3.93	<1	0.35	<10	0.23	848	<2	0.02	3	955	114	2.75	<5	1	53	<5	<0.01	<10	<10	15	<10	243	2
120818	2.0	0.93	238	171	<0.5	<5	2.22	6	16	24	19	4.36	<1	0.28	<10	0.29	1235	<2	0.02	3	1056	31	2.67	<5	2	60	<5	<0.01	<10	<10	20	<10	57	2
120819	5.2	0.70	265	98	<0.5	<5	3.47	6	23	21	40	4.81	<1	0.37	<10	0.18	1302	3	0.01	4	1016	33	4.40	5	2	122	<5	<0.01	<10	<10	20	<10	41	2
120820	1.0	1.97	45	145	<0.5	<5	3.23	1	16	8	34	5.15	<1	0.29	10	0.97	2231	<2	0.02	3	1302	5	1.25	<5	3	69	<5	<0.01	<10	<10	38	<10	99	2
120821	2.6	0.20	255	116	<0.5	<5	5.76	7	10	73	11	2.94	<1	0.16	<10	0.03	1236	2	0.01	3	314	49	3.13	6	1	160	<5	<0.01	<10	<10	5	<10	87	1
120822	1.9	0.35	162	115	<0.5	<5	3.06	4	15	55	15	3.88	<1	0.25	<10	0.09	902	<2	0.01	3	615	16	3.71	<5	2	80	<5	<0.01	<10	<10	11	<10	20	2
120823	2.5	0.42	185	98	<0.5	<5	4.19	4	20	41	16	4.32	<1	0.27	<10	0.15	1344	<2	0.01	4	740	20	4.19	<5	2	139	<5	<0.01	<10	<10	15	<10	11	1
120824	3.0	1.42	296	225	<0.5	<5	3.96	7	24	18	68	5.18	<1	0.29	<10	0.77	1662	<2	0.01	4	1233	48	1.97	<5	2	103	<5	<0.01	<10	10	37	<10	104	2
120825	3.8	1.37	163	101	<0.5	<5	4.41	5	25	12	101	6.13	<1	0.32	<10	0.74	1734	<2	0.01	4	1198	57	4.12	<5	3	121	<5	<0.01	<10	10	47	<10	173	2
120826	27.2	1.57	1791	186	<0.5	<5	4.29	48	21	14	53	5.81	<1	0.28	<10	0.97	1838	<2	0.01	3	1351	141	2.12	13	3	107	<5	<0.01	<10	10	45	<10	476	2
120827	1.2	1.94	56	136	<0.5	<5	6.57	1	23	11	40	5.88	<1	0.23	<10	1.11	2291	<2	0.01	3	1310	13	1.46	<5	3	159	<5	<0.01	<10	13	57	<10	94	2
120828	1.1	1.95	42	167	<0.5	<5	4.07	1	22	7	50	5.86	<1	0.28	<10	1.08	1942	<2	0.01	3	1388	11	1.06	<5	4	111	<5	<0.01	<10	11	63	<10	91	2
120829	22.7	1.08	287	131	<0.5	<5	6.65	62	17	18	185	5.40	2	0.22	<10	0.58	2380	<2	0.01	3	1050	2350	3.46	<5	2	145	<5	<0.01	<10	14	33	68	7078	1
120830	0.8	1.69	21	152	<0.5	<5	6.68	1	20	9	44	5.07	<1	0.23	<10	0.91	2324	<2	0.01	3	1189	31	1.48	<5	3	131	<5	<0.01	<10	12	58	<10	157	1
120831	0.9	1.76	42	137	<0.5	<5	4.91	1	24	10	41	5.48	<1	0.24	<10	1.01	1989	<2	0.01	3	1325	34	1.93	<5	3	121	<5	<0.01	<10	10	58	<10	114	2
120832	1.1	1.80	48	129	<0.5	<5	6.14	2	21	6	38	5.82	<1	0.23	<10	1.05	2463	<2	0.02	3	1286	80	2.27	<5	3	139	<5	<0.01	<10	12	59	<10	183	2
120833	1.2	1.87	21	127	<0.5	<5	6.02	<1	24	5	44	5.43	<1	0.24	<10	0.92	2603	<2	0.01	3	1390	18	1.12	<5	3	148	<5	<0.01	<10	13	56	<10	93	1
120834	0.5	2.05	7	199	<0.5	<5	5.54	1	22	5	51	5.73	<1	0.23	11	0.98	2185	<2	0.02	3	1376	24	0.75	<5	4	139	<5	<0.01	<10	10	73	<10	203	2
120835	3.3	1.01	72	149	<0.5	<5	6.27	3	23	8	50	4.76	<1	0.25	<10	0.49	2551	<2	0.01	3	888	85	2.26	<5	4	146	<5	<0.01	<10	15	30	<10	149	1
120836	1.4	0.97	45	179	<0.5	<5	5.57	1	20	8	47	4.38	<1	0.30	<10	0.49	2284	<2	0.01	3	879	17	2.19	<5	3	94	<5	<0.01	<10	12	27	<10	72	1
120837	2.1	1.28	98	118	<0.5	<5	6.29	3	24	11	36	5.75	<1	0.25	<10	0.61	2572	<2	0.01	2	1051	57	3.41	<5	3	110	<5	<0.01	<10	15	38	<10	134	1
120838	1.6	1.21	93	73	<0.5	5	3.94	2	30	14	27	6.80	<1	0.28	<10	0.57	2170	<2	0.01	3	1208	53	>5.00	<5	3	94	<5	<0.01	<10	16	39	<10	89	2
120839	2.0	1.63	55	155	<0.5	<5	3.76	2	29	8	45	5.73	<1	0.31	<10	0.72	2161	<2	0.01	3	1087	47	3.28	<5	4	97	<5	<0.01	<10	16	53	<10	119	3
120840	18.7	1.08	177	112	<0.5	<5	9.07	11	21	12	45	5.42	<1	0.21	<10	0.47	3546	<2	0.01	3	637	511	3.42	<5	2	217	<5	<0.01	<10	24	32	10	874	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3283RJ**

Date : Sep-30-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120841	2.4	1.62	62	157	<0.5	<5	3.21	2	24	11	62	5.32	<1	0.31	<10	0.70	1958	<2	0.01	3	1142	49	2.44	<5	3	82	<5	<0.01	<10	13	52	<10	154	2
120842	2.5	2.24	35	183	<0.5	<5	3.11	1	29	5	63	6.16	<1	0.31	<10	0.99	2076	<2	0.01	4	1316	28	1.44	<5	4	77	<5	<0.01	<10	13	80	<10	132	2
120843	1.9	1.69	39	140	<0.5	<5	3.92	1	24	8	64	4.94	<1	0.30	<10	0.77	1845	2	0.01	3	1178	18	1.72	<5	3	102	<5	<0.01	<10	12	48	<10	75	2
120844	1.4	1.62	42	155	<0.5	<5	5.74	1	22	4	45	4.96	<1	0.25	<10	0.80	2048	<2	0.01	2	1191	13	2.15	<5	3	146	<5	<0.01	<10	13	51	<10	71	2
120845	1.7	1.69	41	126	<0.5	<5	4.54	1	22	6	44	4.88	<1	0.26	<10	0.79	2048	<2	0.01	2	1228	11	1.59	<5	3	110	<5	<0.01	<10	12	54	<10	77	2
120846	7.0	1.72	54	124	<0.5	<5	5.14	4	23	5	48	4.78	<1	0.27	<10	0.76	2364	<2	0.01	2	1085	116	1.34	<5	3	129	<5	<0.01	<10	13	56	<10	444	2
120847	8.3	0.70	93	128	<0.5	<5	13.94	2	12	20	35	2.55	<1	0.18	<10	0.33	3634	<2	0.01	2	572	61	1.45	<5	2	479	<5	<0.01	<10	17	18	<10	42	<1
120848	3.9	1.67	56	126	<0.5	<5	4.15	1	26	7	64	5.53	<1	0.27	<10	0.90	1716	<2	0.01	3	1253	17	2.92	<5	3	116	<5	0.01	<10	12	49	<10	65	2
120849	4.2	1.48	64	131	<0.5	<5	3.93	1	23	9	80	4.76	<1	0.28	<10	0.69	1738	<2	0.01	3	1203	28	2.31	<5	3	98	<5	0.02	<10	11	50	<10	86	2
120850	<0.2	0.91	<5	254	<0.5	<5	0.48	<1	8	76	1	2.04	<1	0.47	<10	0.59	586	<2	0.06	6	693	4	0.01	<5	2	41	<5	0.11	<10	<10	39	<10	50	2
120851	2.2	1.98	34	110	<0.5	<5	5.09	1	24	7	56	5.37	<1	0.25	<10	0.92	2465	<2	0.01	4	1218	20	1.37	<5	3	134	<5	<0.01	<10	14	62	<10	91	2
120852	6.1	1.67	64	126	<0.5	<5	5.25	16	25	7	130	4.88	<1	0.29	<10	0.71	2294	<2	0.01	3	1145	358	1.85	<5	3	124	<5	<0.01	<10	15	44	16	1743	2
120853	1.1	2.10	22	127	<0.5	<5	4.97	<1	27	3	47	5.23	<1	0.29	<10	0.90	2378	<2	0.01	3	1200	10	0.84	<5	3	129	<5	<0.01	<10	15	58	<10	79	2
120854	3.3	1.65	48	109	<0.5	<5	6.07	1	21	6	39	4.63	<1	0.26	<10	0.72	2487	<2	0.01	2	1136	12	1.32	<5	3	152	<5	<0.01	<10	15	45	<10	58	1
120855	1.3	2.09	21	117	<0.5	<5	4.59	<1	25	2	53	5.01	<1	0.28	<10	0.96	2201	<2	0.01	2	1167	9	0.60	<5	3	133	<5	<0.01	<10	13	58	<10	91	2
120856	0.6	1.38	5	80	<0.5	<5	2.66	<1	15	5	2	3.75	<1	0.20	10	0.59	1937	<2	0.01	2	1183	9	1.15	<5	2	49	<5	<0.01	<10	<10	17	<10	83	1
120857	1.5	1.10	43	91	<0.5	<5	1.47	1	14	6	8	3.43	<1	0.22	<10	0.47	1378	<2	0.01	3	1065	14	1.52	<5	1	30	<5	<0.01	<10	<10	13	<10	84	1
120858	15.4	0.78	68	80	<0.5	<5	5.32	2	10	16	26	3.04	<1	0.19	<10	0.32	2016	<2	0.01	2	763	49	1.97	5	1	106	<5	<0.01	<10	11	12	<10	150	1
120859	2.5	0.89	102	108	<0.5	<5	1.76	2	13	11	7	4.16	<1	0.25	<10	0.33	1152	<2	0.01	3	1009	22	3.20	<5	1	45	<5	<0.01	<10	<10	14	<10	62	2
120860	1.6	0.97	124	127	<0.5	<5	1.23	3	14	18	12	3.84	<1	0.25	<10	0.36	1254	<2	0.01	3	1068	47	2.31	<5	1	37	<5	<0.01	<10	<10	18	<10	114	2
125834	5.3	0.77	843	44	<0.5	<5	0.79	18	15	41	22	8.11	<1	0.40	<10	0.22	538	<2	0.01	4	1027	51	>5.00	<5	3	38	<5	<0.01	<10	12	22	<10	82	4
125835	8.1	0.41	>10000	86	<0.5	<5	2.09	265	15	58	46	3.87	<1	0.32	<10	0.05	641	7	0.01	4	870	71	3.41	186	1	84	<5	<0.01	<10	10	14	<10	103	2
125836	5.0	1.23	450	87	<0.5	<5	0.82	10	25	23	76	5.06	1	0.37	<10	0.48	1074	2	0.01	4	1550	39	3.21	<5	3	41	<5	<0.01	<10	<10	47	<10	99	2
125837	4.1	1.19	359	88	<0.5	<5	2.01	8	21	34	55	5.14	<1	0.35	<10	0.42	1261	3	0.01	3	1426	51	3.27	<5	3	72	<5	<0.01	<10	<10	50	<10	111	2
125838	1.5	1.92	152	158	<0.5	<5	4.35	3	18	17	37	4.88	1	0.32	<10	1.16	2239	<2	0.02	3	1802	36	1.47	<5	4	232	<5	<0.01	<10	<10	71	<10	114	2
125839	2.4	0.26	128	32	<0.5	<5	10.74	3	6	81	37	1.52	<1	0.16	<10	0.10	5462	<2	0.01	3	443	47	1.38	<5	1	276	<5	<0.01	<10	29	8	<10	71	<1
125840	0.8	2.13	58	85	<0.5	<5	4.02	1	21	50	26	4.92	<1	0.24	19	1.56	1308	<2	0.02	13	2599	15	0.58	<5	4	172	<5	0.01	<10	<10	72	<10	122	3
125841	2.7	1.99	362	83	<0.5	<5	3.56	8	23	17	52	5.80	1	0.31	<10	1.27	1929	<2	0.01	4	1860	46	2.19	<5	4	118	<5	0.02	<10	11	95	<10	155	2
125842	1.1	1.98	66	343	<0.5	<5	3.47	1	22	11	37	5.31	1	0.36	12	0.99	1606	<2	0.02	3	1920	16	1.08	<5	5	114	<5	0.01	<10	<10	79	<10	92	3
125843	<0.2	1.20	12	1643	<0.5	<5	2.76	<1	10	56	<1	3.36	<1	0.26	44	0.93	837	<2	0.03	8	2103	11	0.08	<5	3	98	<5	0.01	<10	<10	48	<10	73	5

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3283RJ

Date : Sep-30-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
125844	1.5	1.94	161	202	<0.5	<5	3.23	5	19	19	52	5.05	<1	0.42	16	1.04	1396	<2	0.02	4	1908	52	1.48	<5	5	96	<5	0.01	<10	<10	73	<10	205	4
125845	1.8	2.22	62	112	<0.5	<5	3.58	3	23	12	66	6.06	<1	0.29	<10	1.22	2023	<2	0.02	3	1773	18	1.45	<5	4	120	<5	0.01	<10	13	81	<10	228	2
125846	2.1	2.10	79	97	<0.5	<5	4.66	2	20	9	38	5.49	<1	0.32	<10	1.10	2457	<2	0.02	2	1722	13	1.09	<5	5	151	<5	<0.01	<10	13	75	<10	146	2
125847	6.0	2.26	108	153	<0.5	<5	5.13	2	21	15	47	5.49	<1	0.46	<10	1.06	2428	<2	0.03	2	1751	37	1.43	<5	6	155	<5	0.02	<10	13	92	<10	124	2
125848	3.1	1.03	572	89	<0.5	<5	2.74	13	16	41	41	4.23	<1	0.33	<10	0.36	1079	7	0.01	3	1409	26	2.50	<5	3	98	<5	<0.01	<10	<10	34	<10	76	2
125849	<0.2	1.02	18	338	<0.5	<5	2.65	<1	9	37	5	2.19	<1	0.23	13	0.70	484	<2	0.04	5	1093	8	0.25	<5	2	101	<5	<0.01	<10	<10	31	<10	44	5
125850	<0.2	0.90	<5	242	<0.5	<5	0.44	<1	8	106	<1	2.04	<1	0.47	<10	0.62	566	<2	0.05	5	865	<2	<0.01	<5	2	41	<5	0.14	<10	<10	39	<10	51	2
125851	2.8	2.14	111	127	<0.5	<5	3.45	3	24	17	71	6.22	<1	0.35	<10	1.03	2267	<2	0.01	3	1786	152	1.69	<5	5	127	<5	<0.01	<10	16	85	<10	201	2
125852	3.1	1.76	176	72	<0.5	<5	3.59	5	23	19	55	5.49	<1	0.30	<10	0.82	2234	<2	0.01	3	1845	93	1.76	<5	4	139	<5	<0.01	<10	13	71	<10	235	2
125853	3.8	1.48	368	82	<0.5	<5	3.81	10	22	17	49	5.65	<1	0.34	<10	0.67	2294	<2	0.01	3	1814	127	2.87	<5	4	143	<5	<0.01	<10	14	60	<10	396	2
125854	3.3	1.38	324	88	<0.5	<5	3.09	8	26	16	57	5.86	<1	0.34	<10	0.76	2291	<2	0.01	3	2030	76	2.06	<5	4	147	<5	<0.01	<10	16	62	<10	211	2
125855	7.1	1.03	894	73	<0.5	<5	3.37	20	30	26	103	6.69	<1	0.48	<10	0.31	1430	<2	0.01	4	1973	46	>5.00	<5	4	132	<5	<0.01	<10	11	42	<10	85	3
125856	3.5	1.90	97	66	<0.5	<5	3.68	2	23	12	73	5.42	<1	0.30	<10	0.91	2081	<2	0.01	3	1384	39	1.71	<5	5	174	<5	<0.01	<10	13	74	<10	100	2
125858	3.4	1.31	235	90	<0.5	<5	3.26	6	24	20	59	5.24	<1	0.40	10	0.48	1569	<2	0.01	3	1446	26	3.72	<5	4	154	<5	<0.01	<10	<10	48	<10	93	2
125859	2.3	1.93	45	77	<0.5	<5	3.73	3	18	11	62	5.20	<1	0.35	11	0.72	1909	<2	0.01	2	1356	18	1.30	<5	4	151	<5	<0.01	<10	10	64	<10	387	2
125860	2.5	1.54	219	106	<0.5	<5	3.92	6	18	22	36	4.52	<1	0.37	<10	0.55	1628	<2	0.01	2	1231	62	1.81	<5	4	157	<5	<0.01	<10	<10	51	<10	100	2
125861	<0.2	1.54	5	736	<0.5	<5	4.74	<1	14	43	11	3.83	<1	0.26	35	1.39	1038	<2	0.03	10	2204	6	0.10	<5	5	372	<5	<0.01	<10	<10	35	<10	116	3
125862	1.5	1.93	48	141	<0.5	<5	5.17	2	19	10	39	4.58	<1	0.37	10	0.83	2371	<2	0.02	2	1299	18	0.82	<5	5	212	<5	<0.01	<10	12	68	<10	149	2
125863	2.3	1.85	47	89	<0.5	<5	4.89	1	19	7	65	4.67	<1	0.31	<10	0.80	2231	<2	0.01	2	1273	16	0.91	<5	4	238	<5	<0.01	<10	12	58	<10	131	2
125864	3.0	0.84	233	109	<0.5	<5	8.82	6	16	18	38	3.38	<1	0.31	<10	0.25	2143	3	<0.01	2	879	25	2.39	<5	2	182	<5	0.02	<10	12	27	<10	47	1
125865	1.7	1.46	107	93	<0.5	<5	0.53	3	17	10	48	3.83	<1	0.32	<10	0.67	673	<2	0.01	3	711	30	1.12	<5	2	21	<5	0.01	<10	<10	41	<10	55	2
125867	2.1	1.68	146	106	<0.5	<5	0.41	4	18	21	48	4.35	<1	0.34	<10	0.96	839	3	0.01	5	1045	53	1.44	<5	2	23	<5	<0.01	<10	<10	41	<10	145	2
125868	3.6	1.16	416	126	<0.5	<5	0.82	10	23	21	74	3.91	<1	0.36	<10	0.46	658	<2	0.01	6	1283	46	2.13	6	2	37	<5	<0.01	<10	<10	36	<10	57	2
125869	1.9	1.17	355	152	<0.5	<5	0.40	9	13	22	32	3.16	<1	0.41	<10	0.39	529	<2	0.01	5	925	22	1.18	<5	2	24	<5	<0.01	<10	<10	25	<10	51	2
125871	1.7	1.46	121	118	<0.5	<5	2.01	4	15	14	29	4.17	<1	0.29	<10	0.70	1238	<2	0.02	2	1238	50	1.34	<5	2	120	<5	<0.01	<10	<10	43	<10	175	2
125872	0.8	1.79	14	112	<0.5	<5	4.13	1	14	11	23	4.01	<1	0.29	<10	0.92	1631	<2	0.02	2	1105	12	0.54	<5	3	181	<5	<0.01	<10	<10	54	<10	110	1
125873	1.2	1.64	28	105	<0.5	<5	2.44	3	15	11	41	4.12	<1	0.27	<10	0.91	1453	<2	0.02	2	1178	62	0.89	<5	2	113	<5	<0.01	<10	<10	45	<10	291	1
125874	4.9	1.38	156	129	<0.5	<5	1.09	9	16	18	64	4.47	<1	0.33	<10	0.65	941	<2	0.01	2	1135	174	2.39	<5	2	54	<5	<0.01	<10	<10	32	<10	722	2
125875	>200.0	0.60	463	181	<0.5	131	0.50	19	7	19	7246	2.12	4	0.15	<10	0.55	283	444	0.03	4	317	980	1.20	1386	2	74	<5	0.05	<10	<10	21	<10	895	2
125876	3.7	1.93	36	106	<0.5	<5	1.45	3	19	9	45	5.00	<1	0.27	<10	1.03	1571	<2	0.01	2	1131	104	0.94	<5	2	89	<5	<0.01	<10	11	55	<10	368	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3283RJ**

Date : Sep-30-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
125877	36.8	1.05	414	85	<0.5	<5	0.84	11	14	27	75	4.86	<1	0.38	<10	0.39	720	<2	0.01	2	1022	96	3.68	6	1	61	<5	<0.01	<10	<10	22	<10	233	2
125878	3.0	1.29	296	185	<0.5	<5	1.47	8	14	18	40	3.80	<1	0.29	<10	0.70	1256	2	0.01	2	1054	52	1.14	<5	3	97	<5	<0.01	<10	<10	34	<10	192	2
125879	1.6	0.85	<5	203	<0.5	<5	2.15	<1	8	40	4	1.97	<1	0.23	15	0.60	534	<2	0.03	4	713	6	0.24	<5	3	109	<5	<0.01	<10	<10	18	<10	43	4
125880	2.5	2.07	42	190	<0.5	<5	3.26	1	16	14	34	4.56	<1	0.34	<10	0.91	1641	<2	0.06	2	1140	32	1.26	<5	4	141	<5	0.03	<10	10	64	<10	124	2
125881	1.9	1.73	52	162	<0.5	<5	2.80	2	15	13	32	4.34	<1	0.30	<10	0.84	1578	<2	0.02	2	1039	27	1.26	<5	3	91	<5	0.01	<10	<10	57	<10	149	2
125882	3.1	0.79	285	92	<0.5	<5	5.16	11	11	16	33	2.65	<1	0.26	<10	0.31	1858	<2	0.01	2	684	84	1.71	<5	1	291	<5	<0.01	<10	<10	19	<10	616	1
125883	1.8	1.67	24	145	<0.5	<5	3.58	2	16	4	37	4.23	<1	0.36	<10	0.90	1834	<2	0.01	2	1136	118	0.67	<5	3	231	<5	<0.01	<10	11	49	<10	198	1
125884	1.9	1.31	35	113	<0.5	<5	4.72	2	13	5	31	3.85	<1	0.22	<10	0.73	1871	<2	0.01	1	1103	92	1.10	<5	3	226	<5	0.01	<10	<10	44	<10	173	2
125885	2.5	1.01	178	129	<0.5	<5	2.53	6	12	11	21	3.68	<1	0.35	<10	0.50	1306	<2	0.01	1	940	174	2.32	<5	2	171	<5	<0.01	<10	<10	24	<10	202	2
125886	6.9	0.79	164	95	<0.5	<5	3.52	5	10	21	22	2.95	<1	0.25	<10	0.37	1507	<2	0.01	1	779	85	2.00	<5	2	184	<5	<0.01	<10	<10	17	<10	170	1
125887	4.2	1.04	197	132	<0.5	<5	3.03	5	13	20	38	3.49	<1	0.31	<10	0.48	1482	<2	0.01	3	890	57	2.19	<5	2	99	<5	<0.01	<10	<10	27	<10	105	1
125888	1.9	1.67	81	101	0.5	<5	4.61	2	9	19	13	4.55	<1	0.22	<10	0.94	2747	<2	0.01	1	848	50	1.41	<5	2	458	<5	<0.01	<10	16	38	<10	125	1
125889	1.2	1.18	48	108	<0.5	<5	3.26	1	10	15	11	3.56	<1	0.27	<10	0.77	1924	<2	0.01	1	1015	27	1.40	<5	3	182	<5	<0.01	<10	<10	37	<10	72	2
125890	1.5	1.17	42	94	<0.5	<5	3.06	3	11	11	27	3.40	<1	0.29	<10	0.74	1885	<2	0.01	1	1037	121	1.17	<5	2	171	<5	<0.01	<10	<10	27	<10	252	1
125891	1.2	1.07	52	94	<0.5	<5	4.19	2	9	13	13	2.90	<1	0.32	<10	0.54	2079	<2	0.01	1	926	63	0.92	<5	2	238	<5	<0.01	<10	12	21	<10	112	1
125892	1.0	0.95	40	82	<0.5	<5	5.10	1	8	20	9	2.50	<1	0.31	<10	0.49	1947	<2	0.01	1	766	31	0.90	<5	2	202	<5	<0.01	<10	<10	14	<10	66	1
125893	1.9	0.69	159	90	<0.5	<5	6.67	5	7	29	24	2.72	<1	0.28	<10	0.50	2488	<2	0.01	1	626	82	1.29	<5	2	308	<5	<0.01	<10	14	14	<10	123	1
125894	6.4	1.25	319	78	<0.5	<5	5.77	14	14	10	40	4.03	<1	0.24	<10	0.79	2405	<2	0.01	2	1048	119	1.99	<5	2	233	<5	<0.01	<10	14	36	11	1041	1
125895	2.2	1.36	131	95	<0.5	<5	2.34	4	17	10	37	4.08	<1	0.30	<10	0.87	1547	<2	0.01	2	1127	106	1.75	<5	2	141	<5	<0.01	<10	10	38	<10	152	2
125896	2.5	1.29	145	98	<0.5	<5	1.12	4	13	8	24	4.30	<1	0.28	<10	0.73	1113	<2	0.01	1	1173	69	2.06	<5	2	59	<5	<0.01	<10	<10	40	<10	154	2
125897	2.7	0.99	373	102	<0.5	<5	1.33	9	17	16	22	4.10	<1	0.34	<10	0.50	926	<2	0.01	3	1135	50	3.05	<5	2	67	<5	<0.01	<10	<10	29	<10	95	2
125899	1.8	1.24	77	115	<0.5	<5	2.41	3	14	9	33	4.00	<1	0.29	<10	0.69	1551	<2	0.01	1	1175	74	1.59	<5	3	138	<5	<0.01	<10	<10	39	<10	259	2
125900	<0.2	0.93	<5	264	<0.5	<5	0.50	<1	9	85	1	2.09	<1	0.47	<10	0.60	613	<2	0.05	6	699	4	0.01	<5	2	44	<5	0.12	<10	<10	41	<10	52	2
125901	1.3	1.54	32	97	<0.5	<5	1.88	1	15	5	31	4.47	<1	0.30	<10	0.91	1365	2	0.01	1	1197	30	1.48	<5	3	121	<5	<0.01	<10	<10	46	<10	75	2
125902	2.6	1.62	123	68	<0.5	<5	4.64	4	19	12	58	4.53	<1	0.24	<10	1.10	2125	2	0.01	4	1087	66	1.67	<5	3	241	<5	<0.01	<10	14	54	<10	139	1
125903	2.5	1.76	156	66	<0.5	<5	3.56	5	21	8	52	4.87	<1	0.26	<10	1.23	2296	2	0.01	5	1174	82	1.59	<5	4	170	<5	<0.01	<10	13	63	<10	204	2
125904	2.8	2.51	95	66	<0.5	<5	4.15	3	32	12	70	6.55	<1	0.31	<10	1.57	2574	7	0.01	10	1171	63	1.80	<5	5	192	<5	<0.01	<10	17	89	<10	259	2
125905	2.9	0.56	117	56	<0.5	<5	6.69	4	11	34	19	2.92	<1	0.23	<10	0.34	3308	<2	0.01	2	637	241	2.04	<5	2	339	<5	<0.01	<10	15	15	<10	148	<1
125906	1.2	2.02	69	84	<0.5	<5	5.64	2	19	6	28	5.04	<1	0.30	<10	1.01	2676	<2	0.01	2	1439	38	1.17	<5	4	224	<5	<0.01	<10	16	61	<10	126	1
125907	0.8	1.39	549	127	0.9	<5	7.70	14	13	12	36	2.92	<1	0.39	<10	0.54	2322	<2	0.01	2	1244	29	0.55	<5	3	212	<5	<0.01	<10	<10	33	<10	156	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3283RJ

Date : Sep-30-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
125908	1.3	1.68	1426	148	<0.5	<5	7.77	36	14	19	14	3.41	<1	0.34	12	0.80	3486	9	0.03	4	1295	41	0.51	7	3	173	<5	0.09	<10	14	45	<10	200	3
125909	0.7	1.98	330	113	<0.5	<5	4.90	8	17	23	18	4.20	<1	0.29	12	1.21	2180	<2	0.05	6	1495	31	0.48	<5	4	126	<5	0.15	<10	<10	54	<10	137	7
125910	0.9	1.63	59	133	<0.5	<5	3.34	2	14	5	27	3.93	<1	0.38	<10	0.65	1914	<2	0.03	2	1361	45	1.14	<5	2	101	<5	0.07	<10	<10	37	<10	137	1
125911	1.1	2.84	40	176	<0.5	<5	4.20	3	21	8	43	5.23	<1	0.49	<10	1.18	2412	<2	0.11	2	1348	37	1.45	<5	4	121	<5	0.09	<10	13	61	<10	336	2
125912	0.6	2.01	16	91	<0.5	<5	10.00	1	16	20	25	3.51	<1	0.30	<10	1.05	2681	<2	0.05	5	1225	21	0.43	<5	4	201	<5	0.11	<10	11	62	<10	106	3
125913	0.9	3.09	39	93	<0.5	<5	14.96	2	12	8	31	4.29	<1	0.27	<10	1.20	3551	<2	0.09	1	820	29	0.66	<5	4	365	<5	0.09	<10	18	69	<10	146	3
125917	1.8	2.11	54	84	<0.5	<5	4.59	1	21	5	57	5.50	<1	0.24	<10	1.12	2270	<2	0.02	2	1450	21	1.07	<5	5	184	<5	<0.01	<10	12	92	<10	110	2
125918	2.4	2.05	82	111	<0.5	<5	4.47	2	25	4	63	5.70	<1	0.39	<10	0.92	2243	<2	0.01	3	1543	32	1.66	<5	5	167	<5	0.01	<10	13	67	<10	112	2
125919	2.0	3.34	53	132	<0.5	<5	3.91	1	35	12	87	6.60	<1	0.36	<10	1.27	2351	<2	0.16	4	1818	39	1.65	<5	9	98	<5	0.09	<10	<10	156	<10	143	4
125920	<0.2	1.06	<5	778	<0.5	<5	3.20	<1	9	19	<1	2.26	<1	0.22	16	0.75	561	<2	0.03	5	872	3	0.03	<5	2	111	<5	<0.01	<10	<10	27	<10	50	4
125921	1.3	2.38	29	245	<0.5	<5	5.58	1	25	5	67	6.11	<1	0.35	11	1.10	2426	<2	0.04	3	1794	57	0.89	<5	8	301	<5	0.01	<10	13	107	<10	199	2
125922	1.2	1.85	43	130	<0.5	<5	5.21	1	24	6	73	5.31	<1	0.31	<10	0.94	2262	<2	0.02	2	1670	27	0.88	<5	6	343	<5	<0.01	<10	12	82	<10	167	2
125923	2.2	2.06	34	190	<0.5	<5	4.73	2	27	4	70	5.70	<1	0.36	<10	0.96	2516	<2	0.01	3	1735	54	1.29	<5	5	241	<5	<0.01	<10	14	78	<10	253	2
125924	2.8	1.91	64	131	<0.5	<5	5.54	2	21	6	63	5.24	<1	0.34	<10	0.84	2586	<2	0.01	2	1566	35	1.14	<5	5	263	<5	<0.01	<10	14	70	<10	174	2
125925	0.6	1.13	6146	25	<0.5	16	6.55	152	199	13	79	4.09	<1	0.05	13	0.26	817	13	0.09	36	1295	14	1.57	<5	2	104	<5	0.05	<10	<10	43	<10	106	9
125926	2.4	1.87	82	141	<0.5	<5	4.34	3	30	7	79	5.41	<1	0.34	<10	0.82	2041	<2	0.01	4	1582	38	1.41	<5	5	226	<5	<0.01	<10	13	72	<10	194	2
125927	<0.2	1.64	<5	657	<0.5	<5	3.70	<1	17	52	13	4.60	<1	0.25	40	1.64	825	<2	0.05	11	2594	8	0.11	<5	6	234	<5	0.01	<10	<10	52	<10	129	4
125928	0.7	2.24	32	373	<0.5	<5	4.82	<1	28	24	62	5.18	<1	0.60	20	1.36	1421	<2	0.02	8	2132	10	0.56	<5	10	212	<5	0.04	<10	<10	97	<10	90	4
125929	3.9	1.03	2267	121	<0.5	<5	3.92	55	17	12	40	3.81	<1	0.37	<10	0.31	1295	2	0.01	2	1077	26	2.64	52	3	162	<5	<0.01	<10	<10	36	<10	59	2
125930	1.8	1.83	94	117	<0.5	<5	5.89	3	21	7	75	4.68	<1	0.35	<10	0.76	1875	<2	0.01	2	1340	40	1.25	<5	5	236	<5	0.01	<10	10	77	<10	68	2
125931	1.4	1.83	352	123	<0.5	<5	5.05	9	22	3	67	4.77	<1	0.37	<10	0.74	1733	<2	0.01	2	1377	20	1.41	<5	4	195	<5	0.01	<10	10	78	<10	70	2
125932	2.6	1.29	387	125	<0.5	<5	5.29	10	22	5	57	4.44	<1	0.39	<10	0.45	1966	<2	0.01	3	1321	39	2.86	9	3	213	<5	0.02	<10	<10	47	<10	83	2
125933	5.0	0.60	1309	121	<0.5	<5	6.62	33	25	7	47	4.45	<1	0.39	<10	0.11	2082	<2	0.01	4	1261	49	>5.00	35	3	293	<5	<0.01	<10	15	17	<10	54	2
125934	2.3	1.78	201	115	<0.5	<5	4.84	5	18	5	38	4.55	<1	0.35	<10	0.82	1777	<2	0.01	2	1213	21	1.48	<5	4	208	<5	0.01	<10	10	59	<10	70	2
125935	2.6	2.00	61	141	<0.5	<5	4.50	2	20	5	62	4.91	<1	0.40	<10	0.91	1804	<2	0.01	2	1272	19	1.33	<5	4	205	<5	<0.01	<10	12	61	<10	90	2
125936	4.5	1.01	316	138	<0.5	<5	6.18	8	25	13	56	3.49	<1	0.33	<10	0.41	1569	<2	0.01	3	999	39	2.40	<5	2	194	<5	<0.01	<10	<10	31	<10	148	1
125937	3.8	0.75	305	127	<0.5	<5	4.23	8	18	17	29	4.94	<1	0.33	<10	0.41	1186	<2	0.01	3	1081	85	>5.00	<5	3	162	<5	<0.01	<10	10	21	<10	178	2
125938	2.2	1.05	89	146	<0.5	<5	3.97	3	19	29	16	4.65	<1	0.35	<10	0.66	1419	<2	0.01	4	1218	158	4.36	<5	3	173	<5	<0.01	<10	11	27	<10	140	2
125939	17.5	0.48	351	146	<0.5	<5	0.86	11	15	36	36	3.35	<1	0.30	<10	0.12	450	2	0.01	2	710	214	3.61	8	1	47	<5	<0.01	<10	<10	10	<10	357	1
125940	12.9	0.30	328	100	<0.5	<5	1.18	34	11	56	58	4.27	<1	0.21	<10	0.05	389	3	0.01	4	511	359	>5.00	21	1	62	<5	<0.01	<10	<10	7	39	4102	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3283RJ

Date : Sep-30-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
125941	17.8	0.69	214	77	<0.5	6	1.12	29	18	34	94	5.59	<1	0.35	<10	0.23	472	<2	0.01	4	1136	718	>5.00	7	2	55	<5	<0.01	<10	<10	19	34	3543	3
125942	10.1	0.77	155	79	<0.5	9	1.81	6	18	43	24	5.74	<1	0.36	<10	0.50	830	11	0.01	4	1132	77	>5.00	6	3	128	<5	<0.01	<10	10	19	<10	383	3
125943	2.3	1.37	151	132	<0.5	5	4.04	4	18	22	45	5.32	<1	0.36	<10	0.93	1468	<2	0.01	2	1153	34	4.85	<5	4	191	<5	<0.01	<10	13	34	<10	153	2
125944	0.8	1.75	74	158	<0.5	<5	3.33	1	19	22	26	5.24	<1	0.37	<10	1.26	1315	<2	0.01	2	1200	18	3.91	<5	4	143	<5	<0.01	<10	11	49	<10	59	2
125951	<0.2	1.11	<5	581	<0.5	<5	2.82	<1	9	28	15	1.92	<1	0.28	18	0.74	485	<2	0.04	4	791	17	0.30	<5	3	101	<5	0.01	<10	<10	32	<10	50	6
125952	1.4	1.57	101	176	<0.5	<5	6.87	3	15	20	34	4.70	<1	0.39	<10	0.74	2169	<2	0.01	2	1020	57	2.91	<5	5	212	<5	0.01	<10	15	48	<10	97	2
125953	1.4	1.68	58	173	<0.5	<5	3.92	2	13	19	46	4.05	<1	0.37	<10	0.79	1568	<2	0.01	2	1087	42	1.51	<5	3	134	<5	<0.01	<10	<10	39	<10	127	2
125954	1.5	1.47	80	209	0.7	<5	2.85	3	12	21	29	3.85	<1	0.38	<10	0.68	1362	<2	0.01	2	1085	68	1.62	<5	3	86	<5	<0.01	<10	<10	27	<10	281	2
125955	<0.2	0.37	6	225	<0.5	<5	1.22	<1	2	60	4	0.68	<1	0.29	13	0.04	609	2	0.05	1	133	33	0.17	<5	1	58	15	<0.01	<10	<10	3	<10	35	6
125956	2.8	1.25	192	77	<0.5	6	1.01	5	26	27	60	6.94	<1	0.35	<10	0.52	1003	<2	0.01	4	1279	119	>5.00	<5	3	41	<5	<0.01	<10	14	35	<10	168	3
125957	2.8	2.09	148	139	<0.5	<5	3.27	6	22	13	51	5.90	<1	0.28	<10	1.15	2185	<2	0.01	2	1311	186	2.79	<5	5	138	<5	<0.01	<10	14	73	<10	473	2
125958	2.2	1.83	120	139	<0.5	<5	5.34	5	19	16	39	5.26	<1	0.26	<10	1.07	2187	<2	0.01	2	1229	115	2.69	<5	4	189	<5	<0.01	<10	14	63	<10	301	2
125959	2.9	1.84	163	145	<0.5	<5	1.23	6	20	16	44	5.47	<1	0.27	<10	1.09	1334	<2	0.01	2	1283	103	2.82	<5	4	62	<5	<0.01	<10	<10	62	<10	301	2
125960	2.4	1.92	73	131	<0.5	<5	4.42	6	15	15	51	4.49	<1	0.26	<10	1.21	2009	<2	0.01	1	1123	46	1.56	<5	3	163	<5	<0.01	<10	12	49	<10	634	1
125961	2.7	0.99	216	129	<0.5	<5	4.21	7	16	15	70	3.48	<1	0.26	<10	0.53	1239	<2	0.01	1	1063	50	2.63	<5	3	147	<5	<0.01	<10	<10	26	<10	236	2
125962	1.3	0.55	48	135	<0.5	<5	5.79	2	7	24	7	1.33	<1	0.25	<10	0.32	1286	4	0.01	2	912	27	0.70	<5	3	232	<5	<0.01	<10	<10	18	<10	149	<1
125963	1.2	0.99	78	126	<0.5	<5	5.96	3	12	17	53	3.36	<1	0.23	<10	0.56	1477	<2	<0.01	1	963	34	2.51	<5	3	222	<5	<0.01	<10	<10	24	<10	136	1
125964	1.0	1.30	82	143	<0.5	<5	4.25	3	14	19	80	4.08	<1	0.26	<10	0.73	1348	<2	0.01	1	1085	25	2.74	<5	3	163	<5	<0.01	<10	<10	33	<10	279	2
125965	1.1	1.49	63	139	<0.5	<5	5.96	4	9	12	50	3.48	<1	0.26	<10	0.84	1500	<2	0.01	<1	1091	22	1.36	<5	2	212	<5	<0.01	<10	<10	30	<10	558	1
125966	1.8	1.14	94	110	<0.5	<5	4.96	3	12	19	69	4.60	<1	0.24	<10	0.62	1296	<2	<0.01	1	930	24	3.85	<5	2	199	<5	<0.01	<10	<10	23	<10	208	2
125967	1.0	1.87	54	147	<0.5	<5	3.45	2	11	14	50	4.25	<1	0.28	12	1.00	1194	<2	0.01	1	1147	14	1.28	<5	3	124	<5	<0.01	<10	<10	33	<10	115	2
125968	1.5	1.43	90	142	<0.5	<5	3.63	2	13	17	77	4.53	<1	0.28	<10	0.69	1089	<2	0.01	1	1143	24	2.79	<5	2	129	<5	<0.01	<10	<10	27	<10	54	2
125969	2.4	1.95	171	100	<0.5	<5	7.77	4	20	16	81	5.73	<1	0.18	<10	1.08	2021	<2	<0.01	1	948	20	3.01	<5	4	218	<5	<0.01	<10	16	49	<10	104	2
125970	1.6	1.66	49	158	<0.5	<5	7.36	1	12	17	59	4.24	<1	0.25	<10	0.96	1841	<2	0.01	1	1044	19	1.77	<5	3	261	<5	0.01	<10	12	40	<10	60	2
125971	1.7	1.64	51	132	<0.5	<5	5.50	1	15	18	87	4.30	<1	0.24	<10	1.04	1481	2	0.01	2	1132	18	2.00	<5	3	201	<5	<0.01	<10	10	52	<10	42	2
125972	3.1	1.40	70	153	<0.5	<5	4.71	2	11	16	63	4.04	<1	0.26	<10	0.82	1225	<2	0.01	1	1110	26	2.31	<5	3	185	<5	<0.01	<10	<10	36	<10	51	2
125973	1.9	1.73	89	71	<0.5	<5	3.19	3	17	10	43	4.55	<1	0.25	<10	1.02	1749	2	0.01	2	1173	46	1.40	<5	4	166	<5	<0.01	<10	10	68	<10	109	2
125974	1.5	1.76	190	79	<0.5	<5	3.46	4	20	12	39	5.00	<1	0.27	<10	0.97	1764	6	0.01	3	1199	33	1.66	<5	4	161	<5	<0.01	<10	11	71	<10	74	2
125975	162.7	0.89	181	212	<0.5	92	5.49	6	17	24	3534	3.58	3	0.16	<10	0.19	680	60	0.03	32	512	234	1.31	204	2	180	<5	0.07	<10	<10	23	19	231	9
139256	0.5	1.83	32	121	<0.5	<5	0.26	<1	12	19	34	4.62	<1	0.21	10	1.00	649	<2	0.02	4	1234	10	1.44	<5	3	8	<5	<0.01	<10	<10	46	<10	81	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3283RJ

Date : Sep-30-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139257	0.3	0.97	24	214	0.8	5	4.52	1	32	36	62	6.37	<1	0.29	<10	2.16	1603	<2	0.01	20	1346	23	1.49	<5	26	364	<5	<0.01	<10	12	126	<10	128	3
139258	<0.2	0.58	18	164	0.5	<5	3.10	<1	22	26	48	5.06	<1	0.26	15	1.45	949	<2	0.02	12	1867	16	0.97	<5	9	206	<5	<0.01	<10	<10	53	<10	99	3
139259	0.5	0.46	38	63	<0.5	<5	7.00	1	31	23	85	5.76	<1	0.25	<10	1.84	1612	<2	0.01	13	1626	24	2.10	<5	15	352	<5	<0.01	<10	11	61	<10	115	2
139260	0.6	0.64	47	106	0.6	<5	5.47	2	31	31	81	5.85	<1	0.31	<10	1.50	2002	<2	0.01	14	1358	24	2.00	<5	17	253	<5	<0.01	<10	12	78	<10	191	2
139261	2.1	1.53	501	56	0.8	<5	1.97	18	37	69	128	6.92	<1	0.33	<10	1.11	2303	<2	0.01	20	1694	900	1.49	<5	22	53	<5	<0.01	<10	12	152	<10	731	2
139262	3.0	0.77	1565	407	0.8	<5	2.02	72	29	38	107	6.14	<1	0.33	<10	0.33	2820	<2	0.01	19	1498	613	0.55	<5	16	69	<5	<0.01	<10	14	81	34	2965	2
139263	1.9	1.80	999	235	0.5	<5	1.82	31	33	56	94	7.26	<1	0.29	<10	1.37	2322	<2	<0.01	20	1478	122	1.33	<5	15	57	<5	<0.01	<10	13	131	<10	548	2
139264	2.4	1.14	246	300	0.5	<5	2.67	16	23	38	79	5.44	<1	0.33	<10	0.80	2251	<2	<0.01	15	1419	1116	1.08	<5	12	70	<5	<0.01	<10	11	80	11	927	2
139265	1.3	2.33	290	135	<0.5	<5	5.45	12	24	79	106	6.63	<1	0.25	<10	1.96	2977	<2	<0.01	16	1407	136	1.17	<5	14	148	<5	<0.01	<10	18	136	<10	447	2
139266	1.6	0.98	192	134	0.5	<5	4.73	12	29	35	107	6.63	<1	0.26	<10	1.42	2451	<2	0.01	16	1426	517	1.69	<5	16	230	<5	<0.01	<10	17	95	10	841	2
139267	2.5	2.97	133	181	<0.5	<5	2.52	6	31	69	96	7.55	<1	0.15	<10	2.58	2736	<2	0.01	17	1482	302	0.72	<5	20	66	<5	<0.01	<10	12	219	<10	448	2
139490	1.0	1.26	52	140	<0.5	<5	0.62	2	11	24	25	4.57	<1	0.20	<10	0.66	493	<2	0.02	5	1034	82	2.28	<5	2	22	<5	<0.01	<10	<10	30	<10	177	2
139491	0.6	1.51	43	144	<0.5	<5	0.53	1	12	17	25	4.25	<1	0.21	<10	0.78	544	<2	0.02	5	1122	12	1.37	<5	2	17	<5	<0.01	<10	<10	33	<10	89	2
139492	0.5	1.22	36	117	<0.5	<5	0.56	1	13	30	27	4.55	<1	0.19	10	0.61	450	<2	0.02	5	1114	13	2.26	<5	2	23	<5	<0.01	<10	<10	30	<10	69	2
139493	0.3	2.00	27	106	<0.5	<5	1.44	<1	16	16	35	4.89	<1	0.18	10	1.17	916	<2	0.02	5	1172	7	1.21	<5	3	43	<5	<0.01	<10	<10	44	<10	102	2
139494	0.5	1.53	27	151	<0.5	<5	0.46	<1	14	25	31	4.82	<1	0.18	<10	0.85	560	<2	0.02	5	1145	12	1.78	<5	2	15	<5	<0.01	<10	<10	33	<10	87	2
139495	0.6	1.22	41	192	<0.5	<5	0.28	1	11	13	19	3.90	<1	0.22	<10	0.58	345	<2	0.02	3	1275	18	1.49	<5	2	11	<5	<0.01	<10	<10	27	<10	61	2
139496	0.8	1.01	33	179	<0.5	<5	0.26	1	10	25	36	3.65	<1	0.23	<10	0.46	289	<2	0.02	4	1117	65	1.60	<5	2	11	<5	<0.01	<10	<10	23	<10	69	2
139497	0.9	0.61	44	102	<0.5	<5	0.40	2	8	56	35	3.18	1	0.19	<10	0.26	218	<2	0.01	4	668	300	2.36	<5	1	16	<5	<0.01	<10	<10	14	<10	170	2
139498	0.5	1.37	41	112	<0.5	<5	0.47	1	11	30	21	4.57	<1	0.20	<10	0.79	557	<2	0.01	4	1099	14	2.10	<5	2	13	<5	<0.01	<10	<10	32	<10	76	2
139499	0.4	2.06	34	127	<0.5	<5	0.29	<1	13	20	30	5.00	<1	0.19	11	1.27	879	<2	0.02	5	1271	10	1.19	<5	3	9	<5	<0.01	<10	<10	47	<10	107	2
139500	0.4	0.48	24	254	0.5	<5	3.64	1	26	29	52	5.31	<1	0.24	<10	1.82	1134	<2	0.01	16	1169	27	1.20	<5	17	290	<5	<0.01	<10	<10	66	<10	128	2
139530	0.5	0.80	29	94	<0.5	<5	0.18	<1	12	44	26	4.04	<1	0.17	<10	0.38	368	3	0.02	4	862	34	2.41	<5	2	6	<5	<0.01	<10	<10	21	<10	56	2
139531	0.5	0.86	31	92	<0.5	<5	0.20	1	11	31	24	4.42	<1	0.20	<10	0.40	249	2	0.01	4	1069	29	2.80	<5	2	7	<5	<0.01	<10	<10	23	<10	59	2
139532	0.5	1.19	48	105	<0.5	<5	0.25	1	14	21	34	4.86	<1	0.22	<10	0.53	328	3	0.03	5	1301	20	2.92	<5	3	9	<5	<0.01	<10	<10	35	<10	55	3
139533	0.3	2.12	42	105	<0.5	<5	0.32	1	16	17	31	5.27	<1	0.16	13	1.20	767	<2	0.02	5	1351	9	1.35	<5	4	9	<5	<0.01	<10	<10	55	<10	104	3
139534	0.4	2.07	30	122	<0.5	<5	0.29	<1	15	22	32	5.29	<1	0.23	11	1.08	690	<2	0.02	5	1350	9	1.60	<5	3	8	<5	<0.01	<10	<10	47	<10	89	3
139535	0.2	1.77	8	136	<0.5	<5	0.58	<1	14	17	36	5.11	<1	0.20	10	0.92	737	<2	0.02	5	1362	7	1.96	<5	3	14	<5	<0.01	<10	<10	35	<10	82	3
139536	0.3	1.00	26	121	<0.5	<5	0.13	<1	11	41	23	5.27	<1	0.22	<10	0.38	259	<2	0.02	5	1173	50	3.06	<5	2	5	<5	<0.01	<10	<10	20	<10	79	3
139537	1.1	0.54	34	57	<0.5	6	0.09	<1	12	24	32	7.59	6	0.19	<10	0.13	161	<2	0.01	4	1250	27	>5.00	20	1	5	<5	<0.01	29	13	11	<10	87	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Core

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3283RJ

Date : Sep-30-08

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139538	<0.2	1.78	7	151	<0.5	<5	0.18	<1	11	27	25	4.68	<1	0.24	10	0.82	539	<2	0.02	6	1122	9	1.03	<5	3	7	<5	<0.01	<10	<10	30	<10	83	4
139539	0.3	1.65	33	98	<0.5	<5	0.38	<1	13	19	34	4.50	<1	0.19	10	0.83	675	<2	0.01	5	1304	7	1.20	<5	3	10	<5	<0.01	<10	<10	26	<10	79	3
139540	1.1	0.60	43	110	<0.5	<5	0.03	1	4	47	11	2.87	4	0.20	<10	0.18	131	<2	0.02	2	513	26	0.63	30	1	6	<5	<0.01	<10	<10	13	<10	23	2
SD08-21	<0.2	0.30	<5	27	<0.5	<5	3.43	<1	3	145	6	1.47	<1	0.03	<10	0.77	443	2	0.01	21	390	4	0.03	<5	3	755	<5	<0.01	<10	<10	8	<10	27	<1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3283RD

Date : Sep-30-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120817	3.9	0.83	261	86	<0.5	<5	1.48	7	12	22	14	3.49	<1	0.29	<10	0.21	761	<2	0.01	4	992	103	2.48	<5	1	48	<5	<0.01	<10	<10	13	<10	232	1
120818	2.1	1.02	282	143	<0.5	<5	2.13	7	15	20	18	4.17	<1	0.26	<10	0.29	1206	<2	0.01	3	1194	34	2.59	<5	1	59	<5	<0.01	<10	<10	18	<10	57	2
120819	5.3	0.71	325	46	<0.5	5	3.14	8	22	19	39	4.43	<1	0.35	<10	0.18	1301	3	0.01	5	1189	32	4.35	<5	2	122	<5	<0.01	<10	<10	18	<10	41	2
120820	2.9	0.51	466	125	<0.5	<5	3.34	12	13	51	35	2.82	<1	0.18	<10	0.19	1180	3	0.01	3	642	54	2.34	<5	1	101	<5	<0.01	<10	<10	14	<10	100	1
120821	2.3	0.20	273	104	<0.5	<5	5.16	7	9	60	10	2.65	<1	0.15	<10	0.03	1158	2	0.01	4	351	46	2.88	<5	1	147	<5	<0.01	<10	<10	4	<10	81	1
120822	1.7	0.33	181	47	<0.5	<5	2.53	4	14	44	15	3.32	<1	0.21	<10	0.08	831	<2	0.01	4	683	15	3.44	<5	2	73	<5	<0.01	<10	<10	10	<10	22	1
120823	2.5	0.44	228	43	<0.5	6	3.96	5	20	35	15	4.15	<1	0.26	<10	0.15	1350	<2	0.01	5	862	20	4.21	<5	2	137	<5	<0.01	<10	<10	14	<10	11	2
120824	2.9	1.42	315	153	<0.5	<5	3.42	8	21	16	67	4.63	<1	0.28	<10	0.73	1608	<2	0.01	4	1476	43	1.86	<5	2	99	<5	<0.01	<10	<10	38	<10	100	2
120825	159.8	0.93	230	207	<0.5	91	5.71	7	17	26	3739	3.75	5	0.18	<10	0.20	703	80	0.03	36	704	242	1.44	205	2	183	<5	0.08	<10	<10	25	27	249	11
120826	28.5	1.71	2236	137	<0.5	6	4.03	59	20	15	57	5.63	<1	0.31	<10	1.00	1929	<2	0.01	4	1729	143	2.14	<5	3	113	<5	<0.01	<10	<10	46	<10	481	2
120827	1.1	1.93	68	134	<0.5	7	5.73	1	20	11	40	5.30	<1	0.24	<10	1.04	2279	<2	0.01	4	1567	12	1.46	<5	3	154	<5	<0.01	<10	10	55	<10	88	2
120828	1.1	2.09	56	177	<0.5	7	3.87	1	21	7	52	5.77	<1	0.30	<10	1.10	2059	<2	0.01	4	1807	12	1.07	<5	4	114	<5	<0.01	<10	<10	66	<10	93	2
120829	16.2	1.17	335	83	<0.5	6	6.27	66	16	18	184	5.19	2	0.22	<10	0.58	2392	<2	0.01	3	1247	2332	3.43	<5	2	143	<5	<0.01	<10	17	35	114	7162	2
120830	0.7	1.89	32	158	<0.5	7	6.80	1	21	10	46	5.30	<1	0.26	<10	0.97	2542	<2	0.02	4	1540	33	1.73	<5	3	139	<5	<0.01	<10	17	62	<10	162	2
120831	1.1	1.89	55	139	<0.5	6	4.69	1	22	10	42	5.37	<1	0.25	<10	1.02	2112	<2	0.01	4	1726	34	2.06	<5	3	123	<5	<0.01	<10	<10	60	<10	113	2
120832	1.1	2.22	68	136	<0.5	7	6.28	3	23	7	39	6.00	<1	0.29	<10	1.12	2764	<2	0.02	4	1794	88	2.48	<5	3	153	<5	<0.01	<10	15	65	<10	199	2
120833	1.0	2.25	30	132	<0.5	6	5.91	1	24	11	46	5.45	<1	0.28	<10	0.94	2791	<2	0.02	4	1823	20	1.20	<5	3	150	<5	<0.01	<10	14	58	<10	101	2
120834	7.6	2.36	28	164	<0.5	7	6.68	1	28	4	61	5.81	<1	0.33	<10	0.95	3242	<2	0.02	4	1490	72	0.65	<5	4	146	<5	<0.01	<10	17	67	<10	152	2
120835	3.2	1.09	94	133	<0.5	6	6.19	3	22	9	51	4.82	<1	0.26	<10	0.51	2682	<2	0.01	4	1087	88	2.34	<5	4	151	<5	<0.01	<10	18	33	<10	161	1
120836	1.2	1.01	57	110	<0.5	5	5.37	1	19	8	46	4.31	<1	0.30	<10	0.50	2382	<2	0.01	3	1068	16	2.21	<5	3	96	<5	<0.01	<10	16	30	<10	71	1
120837	2.1	1.34	130	67	<0.5	7	5.99	4	24	12	37	5.57	<1	0.26	<10	0.63	2812	<2	0.01	3	1323	56	3.63	<5	3	118	<5	<0.01	<10	17	40	<10	149	2
120838	1.7	1.52	138	40	<0.5	8	4.54	3	34	17	31	7.52	<1	0.35	<10	0.68	2657	<2	0.01	5	1761	64	>5.00	<5	3	121	<5	0.01	<10	21	48	<10	107	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3298-RA1

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-26-08

We hereby certify the following assay of 22 rock samples submitted Sep-15-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120861	0.97	0.95	2.9
120862	0.16		1.7
120863	0.06		1.2
120864	0.20		2.1
120865	0.38		4.5
120866	0.17		3.2
120867	0.21		2.7
120868	0.26		2.4
120869	2.72		10.1
120870	0.05	0.06	1.6
120871	0.04		1.4
120872	0.03		1.2
120873	0.02		0.9
120874	0.01		1.1
120874A	0.33		2.0
120875	0.01		<0.1
120876	0.06		1.5
120877	0.02		1.2
120878	0.05		1.5
120879	0.07	0.07	1.6
120880	0.01		0.8
120881	0.02		0.9
*0211	2.21		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3298-RA2

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-26-08

We hereby certify the following assay of 22 rock samples submitted Sep-15-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120882	0.01	<0.01	0.6
120883	0.03		0.8
120884	0.03		0.7
120885	0.01		0.6
120886	0.01		0.7
120887	0.04		1.2
120888	0.03		1.7
120889	0.04		1.3
120890	0.13		2.3
120891	0.04	0.03	0.8
120892	0.02		0.7
120893	0.01		0.4
120894	0.02		0.4
120895	0.01		0.6
120896	0.02		0.8
120897	0.02		1.0
120898	0.02		0.5
120899	0.01		0.6
120900	6.56		3.0
120901	0.01	<0.01	0.5
120902	0.03		0.5
120903	0.03		0.3
*0211	2.20		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3298-RA3

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-26-08

We hereby certify the following assay of 22 rock samples submitted Sep-15-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120904	0.15	0.16	1.7
120905	0.10		2.2
120906	0.02		0.8
120907	0.02		1.2
120908	0.03		1.0
120909	0.04		0.6
120910	0.04		0.6
120911	0.07		0.7
120912	0.44		3.5
120913	0.03	0.03	0.7
120914	0.04		0.7
120915	0.05		1.0
120916	0.25		7.5
120917	0.06		2.8
120918	0.06		1.2
120919	0.06		1.8
120920	0.07		1.4
120921	0.08		1.1
120922	0.13		3.2
120923	0.07	0.06	2.2
120924	0.16		3.2
120925	6.56		3.1
*0211	2.23		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3298-RA4

Company: **Ascot Resources Ltd.**
 Project: **Dilworth**
 Attn: **Sue Deane**

Sep-26-08

We hereby certify the following assay of 22 rock samples submitted Sep-15-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %	Zn %
120926	0.17	0.15	3.9		
120927	0.23		2.7		
120928	0.48		4.5		
120929	0.12		1.8		
120930	0.12		1.6		
120931	0.08		2.0		
120932	0.15		3.1		
120933	0.65		19.4		2.72
120934	0.74		38.0	2.37	2.07
120935	0.54	0.50	6.3		
120936	0.56		2.1		
120937	0.53		1.4		
120938	0.57		1.7		
120939	0.58		1.8		
120940	0.57		1.7		
120941	0.79		2.9		
120942	0.76		1.9		
120943	0.59		2.2		
120944	1.46		2.3		
120945	1.08	1.08	2.1		
120946	0.55		1.0		
120947	0.66		1.5		
*0211	2.15				
*CCu-1c				0.35	4.02
*BLANK	<0.01			<0.01	<0.01

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3298-RA5

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-26-08

We hereby certify the following assay of 22 rock samples submitted Sep-15-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120948	0.70	0.71	3.8
120949	0.51		2.5
120950	0.01		<0.1
120951	0.52		1.3
120952	0.80		1.1
120953	0.53		2.6
120954	0.42		3.7
120955	0.38		2.0
120956	0.24		0.8
120957	0.26	0.30	0.9
120958	0.36		0.9
120959	0.24		1.8
120960	0.20		2.1
120961	0.12		2.1
120962	0.39		1.4
120963	0.17		1.4
120964	0.34		1.1
120965	0.33		1.6
120966	0.44		2.0
120967	0.50	0.48	3.5
120968	0.40		2.2
120969	0.43		1.7
*0211	2.12		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3298-RA6

Company: **Ascot Resources Ltd.**
 Project: **Dilworth**
 Attn: **Sue Deane**

Sep-26-08

We hereby certify the following assay of 22 rock samples submitted Sep-15-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
120970	0.24	0.22	2.2	
120971	0.63		3.6	
120972	0.36		2.9	
120973	0.39		5.3	
120974	0.51		4.2	
120975	0.52		0.5	
120976	0.27		3.2	
120977	0.22		3.8	
120978	0.07		2.0	
120979	0.06	0.06	1.2	
120980	0.05		1.3	
120981	0.10		0.8	
120982	0.02		<0.1	
120983	0.05		3.4	
120984	0.23		7.0	2.21
120985	0.72		5.8	2.32
120986	0.56		5.2	
120987	0.32		3.4	
120988	0.30		4.3	
120989	0.09	0.09	2.4	
120990	0.08		1.5	
120991	0.08		1.7	
*0211	2.19			
*CCu-1c				3.96
*BLANK	<0.01			<0.01

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3298-RA7

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-26-08

We hereby certify the following assay of 22 rock samples submitted Sep-15-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
120992	0.10	0.13	4.2
120993	0.07		1.3
120994	0.11		0.7
120995	0.09		1.6
120996	0.11		1.4
120997	0.06		0.7
120998	0.07		1.3
120999	0.15		3.6
121000	<0.01		<0.1
121001	0.10	0.12	2.1
121002	0.07		2.4
121003	0.07		1.7
121004	0.04		2.3
121005	0.17		2.5
121006	0.10		2.2
121007	0.07		1.9
121008	0.07		2.0
121009	0.09		2.0
121010	0.10		2.1
121011	0.07	0.07	1.6
121012	0.11		1.8
121013	0.08		1.4
*0211	2.08		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3298-RA8

Company: **Ascot Resources Ltd.**
 Project: **Dilworth**
 Attn: **Sue Deane**

Sep-26-08

We hereby certify the following assay of 22 rock samples submitted Sep-15-08

Sample Name	Au g/tonne	Au-check g/tonne	Ag g/tonne	Ag g/tonne	Zn %
121014	0.16	0.15	1.9		
121015	0.13		1.6		
121016	0.06		1.4		
121017	0.14		2.8		
121018	0.36		2.9		
121019	0.34		5.2		
121020	0.26		3.3		
121021	0.24		3.7		
121022	0.37		24.5		1.10
121023	0.23	0.22	3.7		
121024	0.21		1.8		
121025	0.11		>200	765.7	
121026	0.20		3.5		
121027	0.12		3.3		
121028	0.11		3.5		
121029	0.20		4.5		
121030	0.12		3.2		
121031	0.08		4.6		
121032	1.65		>200	238.4	
121033	0.94	0.89	177		1.16
121034	0.19		5.4		
121035	0.17		3.4		
*0211	2.11				
*CCu-1c				129.9	4.02
*BLANK	<0.01			<0.1	<0.01

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3298-RA9

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-26-08

We hereby certify the following assay of 22 rock samples submitted Sep-15-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121036	0.19	0.18	2.2
121037	0.30		4.3
121038	0.50		2.7
121039	0.38		1.9
121040	0.58		2.1
121041	0.29		2.0
121042	0.17		3.2
121043	0.43		2.9
121044	0.31		1.3
121045	0.55	0.56	1.2
121046	0.48		2.0
121047	0.70		2.6
121048	1.06		2.3
121049	0.61		1.9
121050	<0.01		<0.1
121051	0.54		1.7
121052	0.28		1.8
121053	0.06		0.8
121054	0.54		5.4
121055	0.41	0.42	3.0
121056	0.30		4.1
121057	0.31		3.6
*0211	2.12		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3298-RA10

Company: **Ascot Resources Ltd.**
 Project: **Dilworth**
 Attn: **Sue Deane**

Sep-26-08

We hereby certify the following assay of 22 rock samples submitted Sep-15-08

Sample Name	Au g/tonne	Au-check g/tonne	Ag g/tonne	Ag g/tonne
121058	0.40	0.37	3.1	
121059	0.52		2.8	
121060	0.40		2.6	
121061	0.46		2.3	
121062	0.44		2.2	
121063	0.53		2.0	
121064	0.64		2.9	
121065	0.58		2.8	
121066	0.83		6.0	
121067	0.42	0.44	4.1	
121068	0.39		2.8	
121069	0.63		6.2	
121070	0.91		5.8	
121071	0.57		5.5	
121072	0.70		4.7	
121073	0.37		2.8	
121074	0.23		4.3	
121075	0.10		>200	768.9
121076	0.13		4.1	
121077	0.25	0.22	4.1	
121078	0.15		3.0	
121079	0.21		2.8	
*0211	2.15			
*CCu-1c				129.9
*BLANK	<0.01			<0.1

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3298-RA11

Company: **Ascot Resources Ltd.**
 Project: **Dilworth**
 Attn: **Sue Deane**

Sep-26-08

We hereby certify the following assay of 22 rock samples submitted Sep-15-08

Sample Name	Au g/tonne	Au-check g/tonne	Ag g/tonne	Pb %
121080	0.19	0.19	2.2	
121081	0.38		2.2	
121082	0.20		1.4	
121083	0.26		4.3	
121084	0.32		5.8	
121085	0.17		1.5	
121086	0.51		10.4	
121087	0.48		7.0	
121088	0.12		2.3	
121089	0.21	0.18	4.4	
121090	0.26		2.4	
121091	0.27		5.2	
121092	0.09		2.1	
121093	0.07		1.2	
121094	0.65		3.1	
121095	0.24		17.9	1.20
121096	0.48		2.7	
121097	0.35		2.5	
121098	0.18		2.4	
121099	0.11	0.13	1.9	
121100	0.02		<0.1	
121101	0.09		1.9	
*0211	2.18			
*CCu-1c				0.34
*BLANK	<0.01			<0.01

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3298-RA12

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deane**

Sep-26-08

We hereby certify the following assay of 22 rock samples submitted Sep-15-08

Sample Name	Au g/tonne	Au-check g/tonne	Ag g/tonne
121102	0.10	0.09	1.7
121103	0.06		1.3
121104	0.37		1.1
121105	0.26		2.5
121106	0.17		2.7
121107	0.31		2.3
130001	0.02		<0.1
130002	0.02		<0.1
130003	0.01		<0.1
130004	0.01	<0.01	0.3
130005	0.01		<0.1
130006	0.01		0.2
130007	<0.01		0.2
130008	0.02		0.2
blk-inhouse			
*0211	2.11		
*BLANK	<0.01		

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3298RJ**

Date : Sep-26-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Rock

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120861	2.9	1.48	234	199	<0.5	<5	1.87	5	19	31	36	5.65	<1	0.38	10	0.59	1577	<2	0.02	4	1428	29	2.85	<5	2	52	<5	<0.01	<10	<10	28	<10	104	2
120862	1.7	1.91	102	124	<0.5	<5	3.01	3	16	15	62	5.56	<1	0.24	<10	1.08	2522	<2	0.02	3	1240	12	1.50	<5	2	72	<5	<0.01	<10	10	37	<10	221	2
120863	1.2	2.06	202	190	<0.5	<5	1.81	4	19	18	23	5.96	<1	0.35	11	1.00	2164	<2	0.02	4	1443	13	1.57	<5	3	45	<5	<0.01	<10	<10	39	<10	109	2
120864	2.1	1.71	340	192	<0.5	<5	1.82	8	18	18	14	5.84	<1	0.34	12	0.72	1847	<2	0.02	3	1526	17	2.11	<5	2	45	<5	<0.01	<10	<10	32	<10	124	2
120865	4.5	0.61	304	158	<0.5	<5	3.77	7	18	49	30	5.28	<1	0.32	<10	0.17	1535	2	0.02	4	967	50	>5.00	<5	2	128	<5	<0.01	<10	<10	15	<10	113	2
120866	3.2	1.27	172	144	<0.5	<5	5.36	3	25	48	61	5.80	<1	0.28	<10	0.77	1995	2	0.01	5	1081	25	3.85	<5	3	192	<5	<0.01	<10	<10	35	<10	46	2
120867	2.7	1.91	132	182	<0.5	<5	8.05	3	28	31	64	6.57	<1	0.38	<10	0.88	2858	2	0.01	4	1298	37	2.67	<5	4	216	<5	0.01	<10	17	55	<10	88	2
120868	2.4	1.69	272	162	<0.5	<5	7.05	7	28	24	56	6.61	<1	0.34	<10	0.88	2396	3	0.01	4	1507	37	3.79	<5	3	203	<5	0.01	<10	11	46	<10	132	2
120869	10.1	2.66	524	136	<0.5	<5	7.07	15	29	21	81	7.60	<1	0.32	<10	1.61	2772	<2	0.02	4	1617	345	2.15	<5	4	169	<5	<0.01	<10	16	74	<10	384	2
120870	1.6	2.35	141	153	<0.5	<5	6.58	3	24	25	64	6.79	<1	0.30	12	1.34	2579	<2	0.02	4	1727	21	1.72	<5	4	154	<5	<0.01	<10	14	67	<10	148	2
120871	1.4	2.44	65	179	<0.5	<5	5.80	1	28	20	71	7.41	<1	0.34	10	1.46	2276	<2	0.01	4	1682	22	2.39	<5	5	140	<5	0.01	<10	14	68	<10	135	3
120872	1.2	2.72	53	130	<0.5	<5	6.54	1	28	13	55	7.28	<1	0.27	10	1.45	2523	<2	0.02	4	1684	12	1.08	<5	4	158	<5	<0.01	<10	14	85	<10	136	2
120873	0.9	2.87	52	169	<0.5	<5	5.58	1	32	17	59	7.48	<1	0.32	10	1.55	2398	<2	0.02	4	1681	15	1.18	<5	5	132	<5	<0.01	<10	14	79	<10	151	3
120874	1.1	2.27	53	151	<0.5	<5	7.13	1	31	16	58	7.41	<1	0.33	<10	1.37	2582	<2	0.02	4	1737	16	3.29	<5	5	158	<5	0.01	<10	15	57	<10	162	2
120874A	2.0	2.21	123	149	<0.5	<5	7.47	3	27	28	65	7.87	<1	0.35	<10	1.26	2875	<2	0.01	4	1682	43	3.97	<5	4	149	<5	<0.01	<10	18	63	<10	170	3
120875	<0.2	1.20	<5	330	<0.5	<5	0.72	<1	11	126	1	2.90	<1	0.63	10	0.85	785	<2	0.06	7	953	3	0.01	<5	3	55	5	0.15	<10	<10	53	<10	68	2
120876	1.5	2.17	87	132	<0.5	<5	7.28	2	25	20	59	6.21	<1	0.29	10	1.25	2875	<2	0.02	5	1712	59	1.82	<5	4	146	<5	<0.01	<10	11	69	<10	145	2
120877	1.2	2.64	42	131	<0.5	<5	7.65	1	27	18	40	7.21	<1	0.31	<10	1.39	3025	<2	0.02	4	1729	24	1.75	<5	4	156	<5	<0.01	<10	16	79	<10	175	2
120878	1.5	2.13	83	145	<0.5	<5	7.16	2	31	18	71	7.16	<1	0.36	<10	1.13	2581	<2	0.01	4	1358	31	2.80	<5	4	145	<5	<0.01	<10	16	55	<10	104	2
120879	1.6	1.71	104	137	<0.5	<5	8.13	2	27	24	46	5.96	<1	0.32	<10	0.97	2573	<2	0.01	4	1208	31	2.39	<5	4	207	<5	<0.01	<10	12	47	<10	110	2
120880	0.8	2.36	61	130	<0.5	<5	8.04	1	29	18	46	6.21	<1	0.33	11	1.36	2433	<2	0.01	5	1700	9	1.34	<5	5	162	<5	<0.01	<10	12	60	<10	80	2
120881	0.9	2.36	63	190	<0.5	<5	6.84	2	30	24	52	7.65	<1	0.31	<10	1.55	2243	<2	0.02	6	1674	29	2.98	<5	5	158	<5	<0.01	<10	15	68	<10	264	3
120882	0.6	1.45	37	103	<0.5	<5	4.29	<1	19	15	29	4.98	<1	0.23	<10	0.96	1496	<2	0.01	3	1113	11	2.10	<5	4	104	<5	<0.01	<10	10	44	<10	52	2
120883	0.8	2.07	24	105	<0.5	<5	4.44	<1	19	8	47	5.25	<1	0.21	<10	1.16	1965	<2	0.02	3	1093	83	0.69	<5	4	112	<5	<0.01	<10	11	66	<10	71	2
120884	0.7	2.12	15	95	<0.5	<5	4.75	<1	20	8	51	5.44	<1	0.20	<10	1.22	2239	<2	0.02	3	1110	9	0.94	<5	4	135	<5	<0.01	<10	13	78	<10	109	2
120885	0.6	1.94	23	112	<0.5	<5	5.19	<1	18	7	44	5.01	<1	0.24	<10	1.14	2006	<2	0.02	3	1170	40	1.14	<5	3	156	<5	<0.01	<10	12	69	<10	79	2
120886	0.7	1.91	38	111	<0.5	<5	3.49	<1	18	8	36	4.98	<1	0.26	<10	1.08	1787	<2	0.02	3	1155	9	1.31	<5	3	95	<5	<0.01	<10	11	62	<10	79	2
120887	1.2	2.11	57	133	<0.5	<5	4.69	<1	22	6	49	5.28	<1	0.29	<10	1.01	2112	<2	0.01	3	1001	17	0.96	<5	3	125	<5	<0.01	<10	13	61	<10	77	2
120888	1.7	1.79	41	116	<0.5	<5	5.68	<1	19	9	57	4.66	<1	0.34	<10	0.81	2243	<2	0.01	2	826	70	1.10	<5	4	138	<5	<0.01	<10	14	54	<10	113	1
120889	1.3	1.47	92	103	<0.5	<5	4.98	1	19	12	50	4.77	<1	0.31	<10	0.64	1683	<2	0.01	2	868	24	2.16	<5	3	104	<5	<0.01	<10	11	43	<10	52	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3298RJ

Date : Sep-26-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Rock

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120890	2.3	1.06	143	108	<0.5	<5	3.35	3	17	27	46	3.92	<1	0.34	<10	0.38	1286	<2	0.01	3	802	25	2.10	<5	3	70	<5	<0.01	<10	<10	33	<10	51	2
120891	0.8	1.41	77	110	<0.5	<5	4.62	1	18	12	46	4.28	<1	0.31	<10	0.69	1507	<2	0.01	2	870	21	1.58	<5	4	119	<5	<0.01	<10	10	46	<10	51	1
120892	0.7	1.78	36	95	<0.5	<5	5.12	<1	21	11	48	4.89	<1	0.30	<10	0.87	1614	<2	0.01	2	988	11	1.08	<5	4	132	<5	<0.01	<10	11	59	<10	48	2
120893	0.4	2.00	11	125	<0.5	<5	5.62	<1	20	7	49	4.92	<1	0.31	<10	0.91	1865	<2	0.01	2	1027	7	0.41	<5	5	159	<5	<0.01	<10	12	71	<10	57	2
120894	0.4	1.87	17	116	<0.5	<5	4.80	<1	21	10	51	4.67	<1	0.29	<10	0.90	1601	<2	0.01	3	950	7	0.55	<5	4	140	<5	<0.01	<10	10	73	<10	67	2
120895	0.6	1.62	20	132	<0.5	<5	3.54	<1	21	6	49	4.46	<1	0.27	<10	0.84	1588	<2	0.01	3	1038	10	0.80	<5	3	124	<5	<0.01	<10	10	58	<10	58	2
120896	0.8	1.95	23	110	<0.5	<5	4.48	<1	20	6	92	4.67	<1	0.24	<10	1.15	1545	<2	0.02	2	1050	8	0.69	<5	4	158	<5	<0.01	<10	<10	72	<10	69	2
120897	1.0	2.07	14	90	<0.5	<5	3.58	<1	20	5	100	4.98	<1	0.17	<10	1.31	1521	<2	0.03	2	1097	130	0.76	<5	5	126	<5	0.01	<10	<10	87	<10	186	2
120898	0.5	1.94	12	100	<0.5	<5	3.48	<1	19	5	59	4.72	<1	0.22	<10	1.12	1034	<2	0.02	2	1122	5	0.76	<5	4	110	<5	<0.01	<10	<10	66	<10	69	2
120899	0.6	2.02	17	108	<0.5	<5	3.75	<1	19	10	66	4.78	<1	0.24	<10	1.17	1068	<2	0.02	2	1268	6	0.69	<5	4	124	<5	<0.01	<10	<10	67	<10	72	2
120900	3.0	1.31	561	150	<0.5	70	7.50	14	46	67	490	5.33	10	0.16	11	0.34	826	102	0.03	70	781	83	2.07	<5	3	111	<5	0.09	<10	<10	40	36	91	12
120901	0.5	1.96	28	117	<0.5	<5	4.11	<1	19	7	48	4.90	<1	0.25	<10	1.12	1111	<2	0.02	2	1234	5	1.02	<5	4	129	<5	<0.01	<10	<10	67	<10	73	2
120902	0.5	1.86	40	143	<0.5	<5	3.50	<1	20	6	45	4.95	<1	0.25	<10	1.05	1025	<2	0.02	2	1228	8	1.34	<5	4	123	<5	0.01	<10	<10	63	<10	72	2
120903	0.3	1.99	20	157	<0.5	<5	4.23	<1	19	9	44	4.92	<1	0.23	<10	1.21	1087	<2	0.03	2	1226	5	0.92	<5	5	147	<5	0.01	<10	<10	73	<10	73	2
120904	1.7	0.96	117	77	<0.5	<5	3.21	14	18	50	126	4.43	<1	0.18	<10	0.80	965	32	0.01	5	770	226	3.13	<5	3	105	<5	<0.01	<10	<10	43	17	1541	2
120905	2.2	0.91	131	78	<0.5	<5	3.47	12	12	43	93	4.38	<1	0.17	<10	0.66	1403	7	0.01	2	761	339	3.18	<5	2	87	<5	<0.01	<10	<10	41	13	1125	2
120906	0.8	1.25	77	78	<0.5	<5	2.89	2	9	43	37	3.88	<1	0.18	<10	0.81	1814	3	0.01	2	941	37	1.30	<5	3	76	<5	<0.01	<10	<10	43	<10	135	2
120907	1.2	1.02	112	66	<0.5	<5	4.09	5	9	51	51	3.35	<1	0.16	<10	0.62	1946	3	0.01	2	827	274	1.41	<5	2	101	<5	<0.01	<10	<10	34	<10	478	1
120908	1.0	1.24	73	74	<0.5	<5	2.92	2	9	59	43	3.67	<1	0.18	<10	0.78	1739	2	0.01	2	846	173	1.17	<5	3	68	<5	0.01	<10	<10	39	<10	164	2
120909	0.6	1.20	79	58	<0.5	<5	3.11	2	9	57	23	3.64	<1	0.17	<10	0.71	1542	2	0.01	2	794	14	1.07	<5	3	64	<5	0.01	<10	<10	37	<10	112	2
120910	0.6	1.14	135	69	<0.5	<5	3.44	3	9	64	21	3.49	<1	0.19	<10	0.65	1725	2	0.01	2	763	13	1.17	<5	3	79	<5	0.01	<10	<10	32	<10	142	2
120911	0.7	1.26	76	70	<0.5	<5	3.07	2	9	41	24	3.64	<1	0.16	<10	0.77	2090	2	0.01	1	887	34	1.11	<5	3	70	<5	0.01	<10	11	37	<10	165	2
120912	3.5	0.56	164	76	<0.5	<5	2.08	22	9	72	116	3.62	<1	0.13	<10	0.34	1214	<2	0.01	2	539	645	3.01	<5	1	36	<5	<0.01	<10	<10	19	26	2163	2
120913	0.7	1.44	62	67	<0.5	<5	1.96	2	11	59	28	4.05	<1	0.18	<10	0.96	2151	2	0.01	2	922	22	1.16	<5	3	58	<5	0.01	<10	<10	43	<10	190	2
120914	0.7	1.32	54	76	<0.5	<5	2.55	2	9	79	27	3.76	<1	0.17	<10	0.83	2054	2	0.01	2	771	40	1.06	<5	3	58	<5	0.01	<10	<10	43	<10	216	2
120915	1.0	1.02	100	67	<0.5	<5	2.75	3	9	73	30	3.54	<1	0.16	<10	0.67	2213	4	0.01	2	672	92	1.73	<5	2	70	<5	<0.01	<10	11	33	<10	273	1
120916	7.5	0.36	106	67	<0.5	<5	11.42	10	7	52	297	2.44	<1	0.14	<10	0.22	3782	2	0.01	1	390	1022	1.86	<5	1	259	<5	<0.01	<10	17	10	14	1184	<1
120917	2.8	0.12	71	36	<0.5	<5	12.51	6	4	54	46	1.39	<1	0.11	<10	0.04	4040	2	0.01	1	291	446	1.37	<5	1	506	<5	<0.01	<10	15	2	<10	708	<1
120918	1.2	1.13	82	60	<0.5	<5	3.41	2	10	59	64	3.91	<1	0.18	<10	0.64	1997	3	0.01	2	788	26	1.77	<5	2	116	<5	<0.01	<10	<10	29	<10	94	2
120919	1.8	0.24	109	45	<0.5	<5	7.54	4	5	53	60	2.29	<1	0.14	<10	0.08	2416	4	<0.01	1	472	176	2.22	<5	1	183	<5	<0.01	<10	<10	5	<10	307	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3298RJ**

Date : Sep-26-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Rock

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120920	1.4	0.32	96	66	<0.5	<5	7.79	4	5	79	40	2.34	<1	0.18	<10	0.16	2333	2	0.01	2	450	117	1.91	<5	1	399	<5	<0.01	<10	<10	6	<10	237	1
120921	1.1	0.43	101	73	<0.5	<5	0.68	3	8	85	60	3.09	<1	0.17	<10	0.20	911	4	0.01	3	620	41	2.43	<5	1	21	<5	<0.01	<10	<10	13	<10	124	1
120922	3.2	0.94	115	129	<0.5	<5	1.83	4	15	77	172	4.75	<1	0.22	<10	0.80	2759	10	0.01	4	936	251	2.54	<5	3	61	<5	<0.01	<10	13	44	<10	297	2
120923	2.2	0.80	143	140	<0.5	<5	3.18	5	13	60	68	3.77	<1	0.20	<10	0.47	2410	8	0.01	3	784	116	2.67	<5	2	77	<5	<0.01	<10	11	27	<10	324	1
120924	3.2	1.18	207	88	<0.5	<5	2.98	6	20	32	203	4.56	<1	0.22	<10	0.77	3013	6	0.02	3	1024	63	2.82	<5	3	77	<5	0.01	<10	16	46	<10	213	1
120925	3.1	1.61	597	174	<0.5	74	9.50	14	49	73	575	6.11	9	0.19	12	0.38	920	106	0.04	76	842	89	2.28	<5	3	119	<5	0.10	<10	<10	43	38	101	13
120926	3.9	0.53	364	109	<0.5	<5	4.36	11	15	37	111	4.34	<1	0.30	<10	0.16	2186	9	0.01	3	677	420	4.67	<5	2	134	<5	0.01	<10	10	15	13	437	2
120927	2.7	2.07	320	108	<0.5	<5	1.86	10	20	28	70	6.76	<1	0.23	<10	1.52	3128	6	0.01	3	1010	145	3.72	<5	4	53	<5	0.02	<10	18	88	<10	355	2
120928	4.5	0.95	429	68	<0.5	<5	12.26	20	8	48	44	3.70	<1	0.14	<10	0.62	3305	5	0.01	1	398	1526	2.31	<5	2	187	<5	<0.01	<10	16	30	14	1178	1
120929	1.8	1.37	117	109	<0.5	<5	3.45	3	13	17	91	4.04	<1	0.34	<10	0.63	1482	5	0.01	1	984	34	1.56	<5	2	87	<5	<0.01	<10	<10	34	<10	139	2
120930	1.6	1.40	91	100	<0.5	<5	3.42	2	13	30	91	4.12	<1	0.32	<10	0.67	1504	4	0.01	2	958	40	1.42	<5	2	83	<5	<0.01	<10	<10	34	<10	131	1
120931	2.0	1.47	86	109	<0.5	<5	2.06	4	19	22	147	5.17	<1	0.35	<10	0.77	1472	5	0.01	2	1242	28	1.92	<5	4	75	<5	<0.01	<10	<10	49	<10	382	2
120932	3.1	1.42	86	109	0.5	<5	1.80	9	18	26	175	4.66	<1	0.36	<10	0.63	1133	6	0.01	2	1210	230	1.88	<5	3	43	<5	<0.01	<10	<10	42	11	888	2
120933	19.4	0.51	220	42	<0.5	<5	7.41	282	13	40	806	5.07	1	0.13	<10	0.31	2205	2	<0.01	1	264	8184	>5.00	<5	1	139	<5	<0.01	<10	11	14	346	>10000	1
120934	38.0	1.13	434	46	<0.5	<5	7.32	237	19	48	1751	10.15	1	0.07	<10	0.91	2658	<2	0.01	1	337	>10000	>5.00	<5	1	110	<5	<0.01	<10	25	27	290	>10000	3
120935	6.3	1.80	149	76	<0.5	<5	4.65	6	12	32	247	4.97	<1	0.20	<10	1.23	2465	6	0.01	1	840	168	1.68	<5	3	88	<5	<0.01	<10	13	60	<10	382	1
120936	2.1	2.27	8	178	<0.5	<5	3.85	2	19	32	382	4.97	<1	0.23	<10	1.42	1596	12	0.03	1	1163	193	0.25	<5	6	152	<5	0.09	<10	<10	89	<10	367	3
120937	1.4	2.05	23	106	<0.5	<5	5.30	1	17	17	119	5.17	<1	0.24	<10	1.19	1740	10	0.03	1	1128	17	0.85	<5	4	156	<5	0.01	<10	<10	80	<10	200	2
120938	1.7	2.13	37	65	<0.5	<5	4.39	1	19	20	205	5.36	<1	0.18	<10	1.25	1833	9	0.03	1	1181	29	0.63	<5	5	115	<5	0.05	<10	10	94	<10	263	2
120939	1.8	2.30	7	69	<0.5	<5	4.74	1	20	18	334	5.21	<1	0.14	<10	1.51	1766	13	0.04	1	1174	11	0.29	<5	6	144	<5	0.10	<10	<10	101	<10	259	4
120940	1.7	2.18	16	61	<0.5	<5	4.03	2	19	31	349	4.76	<1	0.15	<10	1.39	1514	25	0.03	1	1066	26	0.39	<5	4	86	<5	0.14	<10	<10	88	<10	315	5
120941	2.9	1.96	20	49	<0.5	<5	4.11	2	19	20	515	4.57	<1	0.17	<10	1.13	1661	16	0.03	1	1064	19	0.40	<5	4	78	<5	0.13	<10	<10	89	<10	307	3
120942	1.9	2.12	19	47	<0.5	<5	5.06	1	19	22	287	4.74	<1	0.21	<10	1.28	1701	27	0.03	1	1097	14	0.38	<5	4	68	<5	0.12	<10	<10	87	<10	276	3
120943	2.2	2.23	<5	36	<0.5	<5	3.94	1	21	21	519	5.01	<1	0.11	<10	1.33	1602	22	0.04	1	1138	13	0.22	<5	4	77	<5	0.14	<10	<10	98	<10	320	4
120944	2.3	2.19	36	17	<0.5	<5	7.19	6	13	36	345	4.40	<1	0.05	<10	1.09	1350	65	0.02	<1	752	14	0.34	<5	2	81	<5	0.09	<10	<10	54	14	439	7
120945	2.1	2.03	5	38	<0.5	<5	2.79	3	19	20	556	4.03	<1	0.14	<10	1.25	1233	36	0.04	<1	1244	14	0.18	<5	3	79	<5	0.16	<10	<10	84	<10	372	5
120946	1.0	2.50	<5	43	<0.5	<5	3.08	<1	22	24	254	5.34	<1	0.13	<10	1.68	1412	14	0.03	1	1279	13	0.25	<5	4	66	<5	0.15	<10	<10	105	<10	248	3
120947	1.5	2.44	7	51	<0.5	<5	1.98	1	22	23	392	5.12	<1	0.19	<10	1.55	1208	25	0.04	1	1254	13	0.29	<5	4	52	<5	0.17	<10	<10	104	<10	272	3
120948	3.8	1.85	20	35	<0.5	<5	3.19	2	18	44	467	4.15	1	0.10	<10	1.18	1337	21	0.02	2	1148	20	0.30	<5	3	57	<5	0.14	<10	<10	83	<10	324	5
120949	2.5	1.95	14	41	<0.5	<5	4.00	1	20	29	635	4.66	1	0.13	<10	1.30	1534	18	0.02	1	1209	10	0.44	<5	5	104	<5	0.12	<10	<10	95	<10	230	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3298RJ

Date : Sep-26-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Rock

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120950	<0.2	0.95	<5	270	<0.5	<5	0.53	<1	9	115	4	2.34	1	0.48	<10	0.64	606	<2	0.05	6	803	4	<0.01	<5	2	45	5	0.13	<10	<10	44	<10	52	2
120951	1.3	2.05	8	50	<0.5	<5	2.42	1	20	26	281	4.48	1	0.19	<10	1.40	1176	30	0.02	1	1348	9	0.32	<5	4	66	<5	0.17	<10	<10	97	<10	209	3
120952	1.1	2.03	7	38	<0.5	<5	2.59	<1	20	44	204	4.44	<1	0.10	<10	1.44	1154	32	0.03	2	1244	9	0.26	<5	3	66	<5	0.15	<10	<10	93	<10	199	3
120953	2.6	2.07	52	56	<0.5	<5	3.41	2	21	21	217	5.13	1	0.15	<10	1.44	1759	18	0.02	1	1260	13	0.77	<5	5	66	<5	0.16	<10	<10	107	<10	208	4
120954	3.7	1.83	64	62	<0.5	<5	4.01	2	21	28	371	4.87	<1	0.19	<10	1.18	1586	20	0.02	1	1302	13	1.09	<5	5	64	<5	0.15	<10	<10	97	<10	177	4
120955	2.0	2.17	17	68	<0.5	<5	3.78	1	21	30	325	4.03	<1	0.15	<10	0.87	1348	25	0.02	1	1287	11	0.27	<5	3	125	<5	0.19	<10	<10	94	<10	169	5
120956	0.8	2.63	18	22	<0.5	<5	5.73	2	15	43	110	2.74	<1	0.04	<10	0.51	780	19	0.02	1	1249	5	0.10	<5	2	72	<5	0.12	<10	<10	71	13	139	11
120957	0.9	2.52	15	77	<0.5	<5	3.10	1	21	13	118	5.31	<1	0.13	<10	1.95	1459	20	0.02	1	1372	12	0.14	<5	6	91	<5	0.14	<10	<10	106	<10	180	4
120958	0.9	2.55	17	33	<0.5	<5	6.36	1	20	26	142	4.29	<1	0.10	<10	1.67	1199	16	0.02	1	1094	12	0.24	<5	4	136	<5	0.14	<10	<10	92	<10	162	3
120959	1.8	2.59	34	47	<0.5	<5	3.32	1	24	14	227	5.68	<1	0.14	<10	2.03	1568	9	0.03	1	1411	13	0.51	<5	6	80	<5	0.19	<10	10	106	<10	184	3
120960	2.1	2.32	37	77	<0.5	<5	3.92	1	21	11	209	5.46	<1	0.23	<10	1.60	1775	10	0.02	1	1367	19	0.66	<5	5	75	<5	0.11	<10	11	87	<10	199	3
120961	2.1	2.08	19	47	<0.5	<5	11.46	<1	17	11	173	4.74	<1	0.20	<10	1.34	3694	13	0.02	<1	1075	7	0.29	<5	4	345	<5	0.10	<10	21	62	<10	116	2
120962	1.4	1.59	14	20	<0.5	<5	6.30	<1	19	47	211	2.78	<1	0.06	<10	0.72	1000	7	0.02	2	1090	18	0.11	<5	4	246	<5	0.17	<10	<10	55	<10	100	2
120963	1.4	2.59	10	21	<0.5	<5	4.59	<1	23	16	206	5.22	<1	0.04	<10	1.91	1568	13	0.03	1	1279	15	0.13	<5	5	108	<5	0.18	<10	10	94	15	163	4
120964	1.1	2.18	8	66	<0.5	<5	2.86	1	22	26	151	4.82	<1	0.17	<10	1.46	1348	17	0.03	1	1370	9	0.26	<5	4	72	<5	0.16	<10	<10	87	<10	179	3
120965	1.6	2.00	18	64	<0.5	<5	4.31	2	21	19	222	4.54	<1	0.17	<10	1.26	1514	12	0.02	1	1247	12	0.42	<5	5	93	<5	0.17	<10	<10	82	<10	290	3
120966	2.0	2.07	24	58	<0.5	<5	4.46	3	21	17	221	4.82	<1	0.17	<10	1.34	1726	19	0.02	1	1303	13	0.48	<5	4	71	<5	0.17	<10	<10	86	10	343	4
120967	3.5	1.99	56	67	<0.5	<5	3.44	3	20	17	286	5.09	<1	0.22	<10	1.34	1453	21	0.02	1	1325	15	1.14	<5	4	85	<5	0.14	<10	<10	81	<10	236	3
120968	2.2	2.07	46	50	<0.5	<5	3.44	2	22	19	273	4.78	<1	0.13	<10	1.52	1522	21	0.02	1	1296	19	0.64	<5	4	91	<5	0.13	<10	<10	79	<10	251	3
120969	1.7	2.16	46	51	<0.5	<5	2.75	2	22	19	144	4.93	<1	0.13	<10	1.52	1534	9	0.03	1	1341	9	0.72	<5	4	90	<5	0.14	<10	<10	88	<10	194	3
120970	2.2	2.65	24	54	<0.5	<5	2.03	1	24	19	258	5.47	<1	0.12	<10	1.92	1492	32	0.04	2	1374	13	0.53	<5	5	95	<5	0.18	<10	<10	115	<10	241	4
120971	3.6	2.32	36	79	<0.5	<5	3.79	1	21	11	453	5.10	<1	0.19	<10	1.61	1669	32	0.03	1	1239	17	0.42	<5	5	128	<5	0.14	<10	<10	110	<10	294	4
120972	2.9	1.94	108	102	<0.5	<5	5.82	3	19	11	197	4.97	<1	0.35	<10	1.04	2126	23	0.02	1	1212	30	1.29	<5	4	140	<5	0.02	<10	11	65	<10	238	2
120973	5.3	2.15	70	106	<0.5	<5	5.05	2	20	8	404	5.56	<1	0.36	<10	1.18	2163	44	0.02	1	1228	18	1.29	<5	4	110	<5	0.05	<10	13	80	<10	294	2
120974	4.2	2.57	76	131	<0.5	<5	4.61	2	31	6	319	7.38	<1	0.34	<10	1.29	2376	49	0.02	1	1195	23	1.58	<5	6	103	<5	0.03	<10	17	109	<10	420	2
120975	0.5	1.13	5938	28	<0.5	<5	6.69	158	191	14	78	4.18	<1	0.05	12	0.27	825	13	0.08	34	1223	14	1.42	<5	2	102	<5	0.05	<10	<10	44	<10	107	9
120976	3.2	1.56	209	112	<0.5	<5	6.31	5	20	14	157	5.75	<1	0.39	<10	0.80	2459	20	0.01	1	1023	165	3.56	<5	3	101	<5	0.08	<10	13	42	<10	211	2
120977	3.8	1.82	78	123	<0.5	<5	5.10	2	25	14	156	4.90	<1	0.44	<10	0.84	1858	51	0.01	1	1340	71	1.70	<5	4	174	<5	0.12	<10	12	52	<10	240	3
120978	2.0	2.55	25	153	<0.5	<5	4.34	1	28	7	73	6.33	<1	0.42	<10	1.34	2195	7	0.01	1	1258	27	0.91	<5	6	87	<5	0.15	<10	11	100	<10	253	3
120979	1.2	2.55	36	138	<0.5	<5	4.55	1	25	11	64	5.90	<1	0.35	<10	1.48	2899	4	0.01	1	1157	16	0.46	<5	6	94	<5	0.14	<10	15	106	<10	234	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3298RJ

Date : Sep-26-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Rock

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
120980	1.3	0.76	32	273	<0.5	<5	4.82	<1	11	31	116	3.39	<1	0.24	<10	0.72	1245	6	0.02	4	565	64	1.75	<5	4	213	<5	<0.01	<10	<10	19	<10	113	3
120981	0.8	0.74	68	230	<0.5	<5	11.22	1	30	38	117	4.27	<1	0.21	<10	0.57	2424	2	0.02	4	484	23	2.18	<5	3	239	<5	<0.01	<10	13	19	<10	48	3
120982	<0.2	0.98	<5	1433	<0.5	<5	2.67	<1	8	36	5	1.89	<1	0.31	18	0.66	623	<2	0.04	5	756	10	0.15	<5	3	138	<5	<0.01	<10	<10	26	<10	58	6
120983	3.4	2.49	23	227	<0.5	<5	8.23	1	37	41	429	6.27	<1	0.36	<10	1.62	2778	38	0.05	11	1392	68	1.47	<5	17	270	<5	0.06	<10	14	183	<10	369	4
120984	7.0	2.07	124	45	<0.5	<5	3.97	245	35	64	737	8.66	1	0.07	<10	1.75	1916	16	0.01	6	611	133	>5.00	<5	8	93	<5	0.01	<10	19	92	333	>10000	3
120985	5.8	1.70	333	40	<0.5	<5	4.77	376	17	51	423	8.28	3	0.05	<10	1.50	3078	14	<0.01	5	534	325	>5.00	<5	7	116	<5	<0.01	<10	22	78	511	>10000	3
120986	5.2	1.55	348	81	<0.5	<5	5.28	33	18	59	151	8.36	<1	0.19	<10	1.12	2328	20	<0.01	9	654	476	>5.00	<5	6	145	<5	<0.01	<10	19	70	33	2744	3
120987	3.4	1.65	227	145	<0.5	<5	5.53	16	24	134	115	6.79	<1	0.31	<10	1.13	2596	20	0.01	18	838	478	3.85	<5	11	146	<5	0.01	<10	14	103	17	1404	2
120988	4.3	1.79	203	129	<0.5	<5	5.94	17	24	136	212	6.62	<1	0.30	<10	1.11	2657	17	0.01	22	983	350	3.58	<5	10	128	<5	0.02	<10	16	101	19	1519	2
120989	2.4	0.90	78	76	<0.5	<5	3.28	4	10	78	119	3.33	<1	0.21	<10	0.60	2124	3	0.01	3	609	146	1.81	<5	2	81	<5	<0.01	<10	<10	27	<10	459	1
120990	1.5	0.80	94	75	<0.5	<5	3.75	2	7	85	32	2.92	<1	0.23	<10	0.51	2472	2	0.01	2	545	111	1.74	<5	2	123	<5	<0.01	<10	<10	21	<10	162	1
120991	1.7	1.15	102	89	<0.5	<5	3.11	3	9	80	76	3.78	<1	0.19	<10	0.83	2848	3	0.01	3	855	58	1.74	<5	3	124	<5	<0.01	<10	16	39	<10	259	2
120992	4.2	0.89	118	85	<0.5	<5	4.97	7	8	62	71	3.66	<1	0.15	<10	0.59	2455	2	0.01	2	732	441	2.23	<5	3	165	<5	<0.01	<10	14	35	<10	615	1
120993	1.3	1.15	52	68	<0.5	<5	3.59	2	9	53	31	3.45	<1	0.18	<10	0.71	2145	2	0.01	1	861	120	0.92	<5	3	105	<5	0.01	<10	<10	38	<10	234	1
120994	0.7	1.26	46	84	<0.5	<5	3.50	1	9	62	23	3.68	<1	0.18	<10	0.76	2247	2	0.01	2	890	15	0.89	<5	3	109	<5	<0.01	<10	11	43	<10	109	1
120995	1.6	1.02	112	60	<0.5	<5	7.07	4	8	55	14	3.67	<1	0.15	<10	0.62	2729	3	0.01	2	755	125	1.58	<5	2	228	<5	<0.01	<10	15	36	<10	223	1
120996	1.4	0.88	99	65	<0.5	<5	4.01	6	7	112	26	3.11	<1	0.15	<10	0.55	1930	2	0.01	4	626	114	1.34	<5	2	118	<5	<0.01	<10	<10	24	<10	458	1
120997	0.7	0.90	60	49	<0.5	<5	2.96	2	7	62	21	2.95	<1	0.11	<10	0.63	1948	3	0.01	2	573	54	1.04	<5	2	82	<5	<0.01	<10	<10	29	<10	98	1
120998	1.3	0.80	101	67	<0.5	<5	6.38	3	7	81	23	3.22	<1	0.12	<10	0.55	2762	2	0.01	2	541	49	1.70	<5	2	236	<5	<0.01	<10	14	29	<10	163	1
120999	3.6	0.59	122	53	<0.5	<5	5.51	7	6	73	19	2.82	<1	0.12	<10	0.41	2473	4	0.01	2	466	445	1.80	<5	2	191	<5	<0.01	<10	10	21	<10	569	1
121000	<0.2	0.86	<5	261	<0.5	<5	0.53	<1	8	129	2	2.21	<1	0.46	<10	0.59	626	<2	0.05	7	720	6	0.01	<5	2	38	<5	0.12	<10	<10	40	<10	57	2
121001	2.1	0.76	63	47	<0.5	<5	4.36	3	7	94	25	2.87	<1	0.12	<10	0.46	1879	4	0.01	2	484	209	1.20	<5	2	120	<5	<0.01	<10	<10	23	<10	244	1
121002	2.4	0.94	40	38	<0.5	<5	5.64	2	8	105	26	3.09	<1	0.12	<10	0.54	2095	2	0.01	4	555	115	0.86	<5	3	176	<5	<0.01	<10	<10	30	<10	227	1
121003	1.7	1.20	39	69	<0.5	<5	4.31	1	13	64	80	3.87	<1	0.15	<10	0.62	2215	3	0.01	4	916	24	0.74	<5	3	142	<5	<0.01	<10	12	45	<10	162	1
121004	2.3	1.26	60	58	<0.5	<5	5.80	3	10	57	132	3.81	<1	0.16	<10	0.74	2915	6	0.01	3	881	40	1.04	<5	3	135	<5	<0.01	<10	13	51	<10	257	1
121005	2.5	1.37	86	62	<0.5	<5	5.81	3	13	52	68	4.42	<1	0.20	<10	0.72	2628	3	0.01	3	947	47	1.61	<5	3	136	<5	<0.01	<10	14	54	<10	182	1
121006	2.2	1.40	91	50	<0.5	<5	5.85	3	12	45	101	4.21	<1	0.14	<10	0.93	3188	3	0.01	3	824	53	1.43	<5	3	149	<5	<0.01	<10	16	62	<10	200	1
121007	1.9	1.29	48	93	<0.5	<5	8.87	2	10	53	106	3.71	<1	0.16	<10	0.98	3333	2	0.01	2	790	45	0.85	<5	3	274	<5	<0.01	<10	16	50	<10	168	1
121008	2.0	0.54	71	182	<0.5	<5	3.93	2	15	50	105	4.97	<1	0.24	<10	0.90	2001	4	0.01	3	1039	33	1.56	<5	3	154	<5	<0.01	<10	13	38	<10	130	1
121009	2.0	0.59	51	199	<0.5	<5	3.96	2	16	57	107	4.77	<1	0.28	<10	0.82	1748	6	0.01	4	1035	54	1.40	<5	3	143	<5	<0.01	<10	<10	37	<10	173	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3298RJ**

Date : Sep-26-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Rock

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121010	2.1	1.14	92	70	<0.5	<5	6.68	7	14	39	147	4.17	<1	0.22	<10	0.72	2444	4	0.01	3	974	66	0.95	<5	3	143	<5	<0.01	<10	12	38	<10	552	1
121011	1.6	0.69	44	71	<0.5	<5	6.61	2	12	55	100	4.34	<1	0.22	<10	0.45	1990	7	0.01	3	984	51	0.71	<5	3	244	<5	<0.01	<10	<10	24	<10	315	1
121012	1.8	1.49	36	56	<0.5	<5	6.12	3	13	40	98	4.63	<1	0.16	<10	0.81	2324	3	0.01	3	947	13	1.06	<5	3	257	<5	<0.01	<10	14	49	<10	388	1
121013	1.4	1.50	19	78	<0.5	<5	5.42	<1	12	74	80	4.56	<1	0.21	<10	0.85	2123	<2	0.01	4	988	11	0.80	<5	3	144	<5	<0.01	<10	13	51	<10	138	1
121014	1.9	1.48	91	63	<0.5	<5	10.93	3	13	42	76	4.89	<1	0.19	<10	0.68	3484	4	0.01	6	989	20	1.60	<5	3	200	<5	<0.01	<10	18	52	10	182	1
121015	1.6	1.02	29	71	<0.5	<5	>15.00	1	8	33	45	3.16	<1	0.17	<10	0.45	4698	3	0.01	2	742	34	0.76	<5	2	394	<5	<0.01	<10	18	33	25	136	<1
121016	1.4	1.03	42	59	<0.5	<5	>15.00	2	8	43	36	3.12	<1	0.15	<10	0.51	4590	2	0.01	2	648	26	0.80	<5	3	397	<5	<0.01	<10	17	34	<10	157	<1
121017	2.8	1.36	204	90	<0.5	<5	4.49	8	11	62	69	4.26	<1	0.15	<10	0.81	2466	6	0.01	3	876	59	1.50	<5	3	128	<5	<0.01	<10	13	63	<10	425	1
121018	2.9	1.51	344	79	<0.5	<5	8.36	11	15	34	102	5.17	<1	0.15	<10	0.86	3804	18	0.01	3	953	193	2.43	<5	3	222	<5	<0.01	<10	20	74	<10	381	1
121019	5.2	1.85	381	85	<0.5	<5	5.91	38	17	42	247	6.39	<1	0.16	<10	1.18	3506	14	0.01	3	945	637	3.44	<5	4	125	<5	<0.01	<10	19	82	39	3195	2
121020	3.3	1.31	362	116	<0.5	<5	3.24	30	15	55	116	4.83	<1	0.18	<10	0.74	2251	10	0.01	3	907	226	2.66	<5	3	91	<5	<0.01	<10	11	62	29	2447	2
121021	3.7	1.69	317	112	<0.5	<5	3.88	8	16	28	222	5.41	<1	0.17	<10	0.88	2462	9	0.01	3	977	34	1.85	<5	4	87	<5	<0.01	<10	14	82	<10	126	1
121022	24.5	1.27	103	93	<0.5	<5	3.02	106	23	51	1745	4.84	<1	0.15	<10	0.71	2085	8	0.01	3	809	3761	2.99	<5	2	115	<5	<0.01	<10	11	46	130	>10000	1
121023	3.7	1.83	253	112	<0.5	<5	3.46	27	16	53	200	5.72	<1	0.14	<10	1.18	3009	14	0.01	3	834	514	2.50	<5	3	77	<5	<0.01	<10	15	79	28	2369	2
121024	1.8	1.48	240	90	<0.5	<5	3.97	7	12	27	63	4.19	<1	0.12	<10	0.78	2708	7	0.01	2	874	49	1.15	<5	4	84	<5	0.01	<10	11	87	<10	186	1
121025	>200.0	0.70	565	217	<0.5	87	0.63	24	8	21	8058	2.51	6	0.17	<10	0.60	334	522	0.03	6	409	1062	1.34	1590	2	83	<5	0.05	<10	<10	21	<10	1114	2
121026	3.5	1.88	241	126	<0.5	<5	3.54	6	14	38	78	5.06	<1	0.16	<10	1.08	3028	28	0.01	3	1118	47	1.36	<5	4	89	<5	0.01	<10	15	90	<10	171	2
121027	3.3	2.07	204	269	<0.5	<5	5.59	12	16	25	118	5.33	<1	0.20	<10	1.22	3270	7	0.01	3	1095	393	1.36	<5	4	132	<5	0.01	<10	17	78	12	947	2
121028	3.5	2.12	183	94	<0.5	<5	4.82	16	14	20	158	5.45	<1	0.20	<10	1.24	3169	10	0.01	2	1094	123	1.49	<5	4	96	<5	<0.01	<10	17	84	19	1624	2
121029	4.5	1.90	187	110	<0.5	<5	4.03	5	15	34	156	5.18	<1	0.21	<10	1.10	2870	7	0.01	3	1138	174	1.66	<5	3	126	<5	<0.01	<10	16	74	<10	151	2
121030	3.2	2.09	164	97	<0.5	<5	5.67	9	16	23	142	5.34	<1	0.25	<10	1.19	3209	16	0.01	3	1228	474	1.73	<5	3	234	<5	<0.01	<10	18	75	10	726	2
121031	4.6	2.33	111	150	<0.5	<5	5.01	13	17	21	124	5.59	<1	0.25	<10	1.43	3152	8	0.01	3	1197	161	1.52	<5	3	129	<5	<0.01	<10	17	78	18	1430	2
121032	>200.0	2.61	289	83	<0.5	<5	3.91	35	17	26	257	8.55	<1	0.21	<10	1.76	3184	12	0.01	3	1166	4491	4.93	12	4	105	<5	<0.01	<10	22	81	42	3528	3
121033	177.3	1.25	641	71	<0.5	<5	3.38	151	19	40	327	7.83	1	0.15	<10	0.67	2245	13	0.01	3	782	2648	>5.00	11	2	63	<5	0.01	<10	17	43	196	>10000	3
121034	5.4	1.39	96	100	<0.5	<5	2.86	8	12	38	137	4.23	<1	0.20	<10	0.68	1917	26	0.01	1	992	448	1.46	<5	2	63	<5	0.01	<10	<10	41	10	794	1
121035	3.4	1.72	145	122	<0.5	<5	3.44	6	15	34	63	5.13	<1	0.27	<10	0.78	2080	7	0.01	2	1121	106	1.66	<5	2	64	<5	0.01	<10	<10	51	<10	357	2
121036	2.2	1.29	172	69	<0.5	<5	4.97	5	12	39	54	4.25	<1	0.19	<10	0.64	2361	5	0.01	2	798	67	1.98	<5	2	69	<5	0.03	<10	14	43	<10	146	1
121037	4.3	1.66	103	73	<0.5	<5	5.29	5	15	26	301	5.04	<1	0.22	<10	0.76	2032	39	0.01	1	1034	67	1.62	<5	3	100	<5	0.01	<10	10	51	<10	423	2
121038	2.7	2.15	42	85	<0.5	<5	4.48	2	19	19	310	5.19	<1	0.21	<10	1.11	1998	23	0.01	1	1221	26	0.59	<5	4	89	<5	0.07	<10	12	86	<10	282	2
121039	1.9	2.34	28	101	<0.5	<5	4.41	1	22	16	353	5.59	<1	0.22	<10	1.18	1844	23	0.02	1	1286	18	0.56	<5	4	104	<5	0.10	<10	11	84	<10	269	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3298RJ

Date : Sep-26-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Rock

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121040	2.1	2.32	30	74	<0.5	<5	4.11	1	20	17	256	5.45	<1	0.23	<10	1.18	1796	68	0.02	1	1273	14	0.60	<5	5	86	<5	0.12	<10	10	94	<10	233	3
121041	2.0	2.30	25	60	<0.5	<5	4.08	1	20	13	229	5.57	<1	0.19	<10	1.26	1813	25	0.02	1	1316	17	0.66	<5	5	96	<5	0.08	<10	11	96	<10	314	2
121042	3.2	2.50	36	64	<0.5	<5	4.22	3	22	14	342	5.95	<1	0.25	<10	1.38	1861	39	0.03	1	1393	38	0.91	<5	5	136	<5	0.05	<10	12	99	<10	432	2
121043	2.9	2.39	359	51	<0.5	<5	4.32	10	23	13	261	6.06	<1	0.21	<10	1.36	2060	56	0.02	1	1387	18	1.40	<5	4	104	<5	0.10	<10	12	90	<10	326	2
121044	1.3	2.54	165	53	<0.5	<5	4.50	5	23	10	97	5.83	<1	0.16	<10	1.52	1948	37	0.03	1	1334	13	0.74	<5	6	106	<5	0.15	<10	10	113	<10	300	3
121045	1.2	2.70	<5	74	<0.5	<5	3.27	<1	24	13	181	5.96	<1	0.14	<10	1.70	1616	58	0.03	1	1390	12	0.34	<5	6	85	<5	0.17	<10	10	121	<10	325	3
121046	2.0	2.43	7	71	<0.5	<5	3.31	1	22	12	352	5.42	<1	0.21	<10	1.41	1700	80	0.03	1	1384	14	0.57	<5	5	87	<5	0.15	<10	10	101	<10	288	3
121047	2.6	2.31	17	70	<0.5	<5	5.30	2	21	15	384	5.31	<1	0.23	<10	1.19	1858	166	0.02	1	1305	25	0.67	<5	4	172	<5	0.13	<10	12	82	<10	373	3
121048	2.3	2.39	10	78	<0.5	<5	4.11	1	21	17	424	5.17	<1	0.24	<10	1.36	1675	86	0.02	1	1288	22	0.35	<5	5	84	<5	0.14	<10	<10	86	<10	311	3
121049	1.9	2.20	15	77	<0.5	<5	4.98	2	19	10	289	4.80	<1	0.23	<10	1.19	2042	40	0.01	1	1228	17	0.43	<5	3	68	<5	0.11	<10	11	66	<10	340	2
121050	<0.2	1.04	<5	276	<0.5	<5	0.51	<1	9	92	4	2.20	<1	0.49	<10	0.58	642	<2	0.05	6	753	3	<0.01	<5	2	45	<5	0.13	<10	<10	43	<10	57	2
121051	1.7	2.39	15	152	<0.5	<5	5.70	1	19	8	198	5.22	<1	0.25	<10	1.33	2239	45	0.01	1	1263	17	0.49	<5	3	148	<5	0.11	<10	14	69	<10	358	2
121052	1.8	1.51	19	52	<0.5	<5	2.87	1	14	2	167	3.97	<1	0.11	<10	0.83	1477	279	0.01	<1	964	18	0.54	<5	2	75	<5	0.04	<10	<10	41	<10	277	1
121053	0.8	1.62	10	73	<0.5	<5	14.62	<1	7	54	28	3.55	<1	0.18	<10	0.78	3172	6	0.01	1	520	6	0.34	<5	3	896	<5	0.03	<10	17	33	<10	136	1
121054	5.4	1.07	288	88	<0.5	<5	7.48	13	13	44	331	4.34	<1	0.28	<10	0.46	2678	17	0.01	2	784	82	3.14	<5	2	197	<5	0.01	<10	16	31	10	770	1
121055	3.0	1.42	161	116	<0.5	<5	5.83	6	12	24	127	3.94	<1	0.25	<10	0.62	2958	29	0.01	1	912	240	1.35	<5	2	144	<5	<0.01	<10	14	45	<10	403	1
121056	4.1	1.81	110	102	<0.5	<5	5.81	4	15	22	267	4.84	<1	0.26	<10	0.74	2996	41	0.01	1	948	27	1.18	<5	3	167	<5	<0.01	<10	16	55	<10	251	2
121057	3.6	2.03	94	133	<0.5	<5	5.36	18	18	10	178	5.34	<1	0.35	<10	0.81	2790	17	0.01	1	1301	660	1.31	<5	4	187	<5	0.01	<10	16	72	24	1923	2
121058	3.1	1.82	52	142	<0.5	<5	3.68	2	16	11	267	4.32	<1	0.32	<10	0.73	2011	93	0.01	1	1220	29	0.68	<5	4	140	<5	<0.01	<10	<10	63	<10	227	1
121059	2.8	1.73	40	141	<0.5	<5	4.47	3	14	13	216	4.04	<1	0.31	<10	0.74	1890	128	0.01	<1	1036	48	0.69	<5	3	134	<5	<0.01	<10	<10	51	<10	361	1
121060	2.6	1.91	49	102	<0.5	<5	5.21	3	16	13	170	4.61	<1	0.31	<10	0.82	2156	40	0.01	1	1181	23	0.78	<5	4	145	<5	<0.01	<10	11	67	<10	346	2
121061	2.3	1.90	28	96	<0.5	<5	2.82	3	15	8	217	4.41	<1	0.34	<10	0.85	1438	38	0.01	1	1167	38	0.62	<5	2	104	<5	<0.01	<10	10	50	<10	334	2
121062	2.2	1.97	37	119	<0.5	<5	2.99	2	19	9	161	4.63	<1	0.37	<10	0.86	1431	29	0.01	1	1251	36	0.65	<5	3	114	<5	0.01	<10	<10	62	<10	295	2
121063	2.0	1.93	29	114	<0.5	<5	3.38	2	18	8	205	4.53	<1	0.36	<10	0.78	1480	89	0.01	<1	1198	20	0.47	<5	3	105	<5	0.07	<10	10	61	<10	278	2
121064	2.9	2.01	41	116	<0.5	<5	7.72	5	21	8	304	5.03	<1	0.33	<10	0.79	2569	43	0.01	<1	1022	14	0.53	<5	5	251	<5	0.07	<10	14	72	<10	404	2
121065	2.8	1.89	54	125	<0.5	<5	5.87	6	21	9	250	5.10	<1	0.34	<10	0.77	2217	89	0.01	<1	1048	17	0.85	<5	4	186	<5	0.04	<10	14	73	<10	511	2
121066	6.0	1.78	96	128	<0.5	<5	3.90	15	17	17	423	4.66	<1	0.33	<10	0.82	1915	33	0.01	1	1066	902	1.06	<5	3	132	<5	0.01	<10	11	58	18	1530	1
121067	4.1	1.94	256	106	<0.5	<5	6.33	10	19	10	293	5.10	<1	0.33	<10	0.80	2521	77	0.01	<1	1099	25	1.03	<5	3	210	<5	0.04	<10	15	57	11	473	2
121068	2.8	1.01	356	81	<0.5	<5	9.92	11	10	23	140	2.96	<1	0.27	<10	0.42	2771	46	0.01	1	678	34	1.16	<5	2	233	<5	0.01	<10	13	27	<10	230	1
121069	6.2	1.69	142	112	<0.5	<5	4.47	9	14	22	358	4.48	<1	0.36	<10	0.70	2342	40	0.01	1	1019	61	1.16	<5	2	134	<5	0.01	<10	12	47	10	702	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3298RJ

Date : Sep-26-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Rock

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121070	5.8	1.46	140	116	<0.5	<5	7.49	9	16	17	425	4.30	<1	0.28	<10	0.72	3423	36	0.01	1	932	38	1.15	<5	3	239	<5	0.02	<10	17	52	<10	536	1
121071	5.5	0.81	337	82	<0.5	<5	4.14	17	8	45	326	3.04	<1	0.28	<10	0.27	1513	27	0.01	1	600	36	1.89	<5	1	115	<5	<0.01	<10	<10	16	<10	624	1
121072	4.7	1.48	260	105	<0.5	<5	4.88	9	16	25	256	4.81	<1	0.35	<10	0.58	1905	41	0.01	1	1168	37	2.21	<5	3	155	<5	0.01	<10	10	43	<10	298	2
121073	2.8	1.69	111	95	<0.5	<5	5.01	6	17	23	176	4.42	<1	0.32	<10	0.77	2382	15	0.01	1	1178	51	1.04	<5	3	148	<5	<0.01	<10	14	51	<10	416	1
121074	4.3	1.44	213	110	<0.5	<5	4.39	13	16	21	132	4.75	<1	0.28	<10	0.82	3099	14	0.01	2	1203	430	2.64	<5	2	126	<5	<0.01	<10	16	52	14	1069	1
121075	>200.0	0.66	547	209	<0.5	93	0.57	24	8	21	7859	2.49	6	0.16	<10	0.59	330	507	0.03	6	401	1029	1.30	1610	1	79	<5	0.04	<10	<10	20	<10	1088	2
121076	4.1	1.46	132	106	<0.5	<5	4.43	4	16	24	152	4.68	<1	0.29	<10	0.87	3458	17	0.01	2	1048	56	2.46	<5	2	147	<5	0.02	<10	18	46	<10	275	1
121077	4.1	1.29	206	91	<0.5	<5	4.96	7	15	18	149	4.78	<1	0.24	<10	0.78	3464	28	0.01	2	1041	137	2.94	<5	2	154	<5	0.01	<10	20	43	<10	379	1
121078	3.0	1.69	87	81	<0.5	<5	5.03	10	14	24	129	4.81	<1	0.26	<10	1.02	3327	9	0.01	2	1128	263	1.80	<5	3	121	<5	0.05	<10	17	65	17	1228	1
121079	2.8	1.38	98	83	<0.5	<5	6.93	3	14	26	131	4.40	<1	0.26	<10	0.72	3323	7	0.01	3	957	104	1.94	<5	3	173	<5	0.07	<10	17	55	<10	265	1
121080	2.2	1.21	105	87	<0.5	<5	4.96	4	13	30	67	3.78	<1	0.26	<10	0.56	2262	8	0.01	2	936	225	1.64	<5	2	169	<5	0.06	<10	12	47	32	336	1
121081	2.2	1.64	62	94	<0.5	<5	5.28	2	15	22	97	4.14	<1	0.25	<10	0.84	2658	9	0.01	3	989	126	0.89	<5	3	155	<5	0.08	<10	14	56	29	133	1
121082	1.4	1.76	35	100	<0.5	<5	3.69	1	15	21	88	4.39	<1	0.26	<10	0.87	2210	6	0.01	3	968	79	0.78	<5	2	166	<5	0.08	<10	13	55	<10	196	2
121083	4.3	1.36	192	90	<0.5	<5	2.97	8	13	32	187	4.76	<1	0.21	<10	0.84	2240	11	0.01	2	819	1086	2.63	<5	2	80	<5	0.05	<10	12	35	<10	559	2
121084	5.8	1.72	139	101	<0.5	<5	3.26	23	18	22	109	5.54	<1	0.26	<10	1.03	2506	7	0.01	2	1029	2283	2.77	<5	2	86	<5	0.06	<10	16	39	37	2769	2
121085	1.5	1.35	75	103	<0.5	<5	2.58	2	13	29	72	3.90	<1	0.26	<10	0.72	2009	10	0.01	2	1071	43	1.49	<5	2	89	<5	0.07	<10	<10	41	<10	158	1
121086	10.4	1.11	76	71	<0.5	<5	9.00	65	9	19	291	4.33	<1	0.21	<10	0.58	3436	13	0.01	1	737	4168	3.04	<5	2	177	<5	0.05	<10	19	31	98	7559	1
121087	7.0	1.22	59	63	<0.5	<5	7.83	36	10	25	300	3.78	<1	0.18	<10	0.75	3036	3	0.01	1	700	3288	1.90	<5	2	150	<5	0.04	<10	16	32	54	4288	1
121088	2.3	2.07	59	134	<0.5	<5	3.03	9	15	21	102	5.29	<1	0.29	11	1.22	2704	7	0.01	1	1207	583	1.12	<5	2	97	<5	0.01	<10	14	53	15	1145	2
121089	4.4	1.62	54	120	<0.5	<5	4.61	41	12	25	144	4.55	<1	0.26	<10	1.08	3194	4	0.01	2	1018	1238	1.41	<5	2	92	<5	<0.01	<10	16	40	67	5490	1
121090	2.4	0.67	62	81	<0.5	<5	10.99	14	6	22	37	2.49	<1	0.14	10	0.60	4925	2	0.01	1	547	518	0.64	<5	2	210	<5	<0.01	<10	23	27	22	1713	<1
121091	5.2	0.89	159	52	<0.5	<5	9.14	14	8	32	112	4.39	<1	0.12	12	0.59	4193	2	0.01	1	571	1653	2.60	<5	2	159	<5	<0.01	<10	19	43	17	1426	1
121092	2.1	1.07	34	84	<0.5	<5	3.64	2	13	20	200	4.19	<1	0.26	<10	0.77	2257	5	0.01	3	1096	22	0.61	<5	3	94	<5	<0.01	<10	10	53	<10	264	1
121093	1.2	1.58	8	141	<0.5	<5	2.93	<1	14	12	158	4.34	<1	0.20	<10	0.99	1649	4	0.02	3	1222	21	0.23	<5	4	77	<5	0.01	<10	<10	69	<10	188	2
121094	3.1	1.69	28	94	<0.5	<5	3.11	1	15	14	162	4.42	<1	0.22	<10	0.85	1730	5	0.02	3	1106	765	0.90	<5	4	100	<5	0.06	<10	<10	68	<10	158	2
121095	17.9	1.53	79	80	<0.5	<5	3.69	8	17	21	255	5.44	<1	0.24	<10	0.79	2264	3	0.01	3	1125	>10000	3.22	<5	3	75	<5	0.01	<10	12	62	<10	569	2
121096	2.7	2.16	39	106	<0.5	<5	4.24	2	20	21	165	5.32	<1	0.29	<10	1.10	2301	6	0.02	4	1447	64	1.01	<5	5	105	<5	0.11	<10	12	96	<10	238	3
121097	2.5	1.65	66	109	<0.5	<5	3.49	2	14	19	171	4.26	<1	0.24	10	0.88	2224	8	0.02	3	1098	72	0.75	<5	3	72	<5	0.02	<10	11	59	<10	181	2
121098	2.4	1.80	95	98	<0.5	<5	4.62	3	15	17	133	4.67	<1	0.27	10	1.02	2858	3	0.01	3	1273	20	1.14	<5	3	96	<5	0.01	<10	13	61	<10	190	1
121099	1.9	1.84	138	126	<0.5	<5	3.60	4	14	24	133	4.71	<1	0.31	12	0.96	2530	5	0.02	2	1348	29	0.83	<5	3	67	<5	0.04	<10	13	59	<10	197	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth

Sample type: Rock

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3298RJ

Date : Sep-26-08

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121100	<0.2	1.09	<5	298	<0.5	<5	0.59	<1	10	142	2	2.41	<1	0.57	<10	0.66	699	<2	0.07	7	808	6	<0.01	<5	3	55	<5	0.14	<10	<10	45	<10	60	2
121101	1.9	1.85	146	114	<0.5	<5	6.16	4	14	12	95	4.50	<1	0.34	12	0.98	2978	6	0.01	1	1277	23	0.90	<5	3	112	<5	0.04	<10	15	47	<10	188	2
121102	1.7	1.59	41	108	<0.5	<5	7.57	1	14	16	126	4.29	<1	0.39	10	0.72	2582	7	0.01	2	1165	14	0.62	<5	2	122	<5	0.02	<10	<10	40	<10	181	1
121103	1.3	1.82	52	108	<0.5	<5	4.51	2	12	13	78	4.42	<1	0.39	10	0.97	2321	5	0.01	2	1123	14	0.63	<5	2	76	<5	<0.01	<10	11	41	<10	143	1
121104	1.1	1.65	1181	134	<0.5	<5	3.09	33	13	20	83	4.35	<1	0.34	11	0.83	2090	7	0.01	2	1056	12	0.42	<5	2	60	<5	0.01	<10	11	43	<10	155	1
121105	2.5	1.33	189	108	<0.5	<5	5.18	7	14	17	161	4.66	<1	0.25	<10	0.74	2430	19	0.01	3	992	38	1.19	<5	3	68	<5	<0.01	<10	<10	61	<10	318	1
121106	2.7	0.82	82	100	<0.5	<5	3.50	3	19	29	155	5.03	<1	0.32	<10	0.62	2269	10	0.01	4	1214	15	0.95	19	3	75	<5	<0.01	<10	11	51	<10	198	1
121107	2.3	0.78	71	101	<0.5	<5	3.76	2	20	17	209	4.55	<1	0.32	<10	0.64	2143	20	0.01	4	1232	16	0.63	15	3	94	<5	<0.01	<10	<10	43	<10	191	1
130001	<0.2	1.91	24	108	<0.5	<5	4.76	<1	14	33	9	4.92	<1	0.15	16	1.31	1402	<2	0.02	2	1100	9	2.35	<5	3	73	<5	<0.01	<10	<10	35	<10	88	2
130002	<0.2	1.72	9	126	<0.5	<5	5.41	<1	11	25	7	4.30	<1	0.17	15	1.24	1478	3	0.02	2	1209	8	1.93	<5	3	90	<5	<0.01	<10	<10	31	<10	109	2
130003	<0.2	0.31	5	68	<0.5	<5	9.22	<1	6	120	1	2.46	<1	0.11	<10	0.13	1442	<2	0.01	3	454	7	1.74	<5	1	358	<5	<0.01	<10	<10	5	<10	23	1
130004	0.3	3.03	16	145	<0.5	<5	3.17	<1	15	24	11	5.56	<1	0.20	<10	2.04	1548	17	0.02	2	1281	8	1.09	<5	4	76	<5	<0.01	<10	<10	50	<10	128	2
130005	<0.2	2.00	12	111	<0.5	<5	4.83	<1	14	26	16	5.21	<1	0.18	16	1.35	1332	<2	0.01	2	1301	10	2.53	<5	3	119	<5	<0.01	<10	<10	36	<10	111	2
130006	0.2	1.47	15	117	<0.5	<5	5.62	<1	15	28	13	5.35	<1	0.22	15	0.88	1311	<2	0.02	2	1347	16	4.17	<5	3	131	<5	<0.01	<10	<10	26	<10	191	2
130007	0.2	1.46	17	114	<0.5	<5	7.96	<1	12	49	9	5.08	<1	0.19	13	0.90	1633	<2	0.01	2	1101	10	3.45	<5	3	163	<5	<0.01	<10	<10	27	<10	106	2
130008	0.2	2.34	5	160	<0.5	<5	6.03	<1	11	21	13	4.57	<1	0.21	12	1.58	1655	<2	0.01	2	1339	2	0.62	<5	4	134	<5	<0.01	<10	<10	52	<10	82	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Quality Assaying for over 25 Years

Assay Certificate

8V-3374-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 27**
Attn: **Sue Deane**

Oct-03-08

We hereby certify the following assay of 22 core samples submitted Sep-18-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121108	0.22	0.24	4.0
121109	0.11		2.5
121110	0.30		3.7
121111	0.27		2.9
121112	0.10		1.0
121113	0.03		0.6
121114	0.02		0.0
121115	0.03		0.4
121116	0.04		0.4
121117	0.01	0.01	0.3
121118	<0.01		0.3
121119	0.01		0.5
121120	0.02		0.5
121121	0.01		0.3
121122	<0.01		0.4
121123	<0.01		0.5
121124	0.01		0.4
121125	<0.01		0.0
121126	0.02		0.5
121127	0.02	0.02	0.8
121128	0.03		2.5
121129	0.04		1.3
*0211	2.18		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3374-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 27**
Attn: **Sue Deane**

Oct-03-08

We hereby certify the following assay of 22 core samples submitted Sep-18-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne	Pb %	Zn %
121130	0.09	0.09	5.6			
121131	0.32		73.6			
121132	<0.01		0.6			
121133	0.08		1.6			
121134	0.21		3.1			
121135	0.12		1.4			
121136	0.08		1.4			
121137	0.10		1.3			
121138	0.06		0.9			
121139	0.07	0.08	0.6			
121140	0.06		0.8			
121141	0.28		1.4			
121142	0.10		1.4			
121143	0.06		1.4			
121144	0.22		3.1			
121145	0.51		3.1			
121146	0.19		5.0			
121147	0.06		2.4			
121148	0.10		5.3			
121149	0.71	0.70	8.9			
121150	0.14		>200	803.5		
121150A	1.75		>200	233.5	1.93	2.65
*0211	2.22					
*CCu-1c				128.3	0.36	3.92
*BLANK	<0.01			<0.1	<0.01	<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3374-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 27**
Attn: **Sue Deane**

Oct-03-08

We hereby certify the following assay of 22 core samples submitted Sep-18-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121151	0.67	0.62	69.6
121152	0.13		8.5
121153	0.23		6.1
121154	0.87		25.2
121155	0.62		17.8
121156	0.15		4.2
121157	0.44		87.6
121158	0.19		11.4
121159	0.04		3.8
121160	0.14	0.16	2.8
121161	0.32		3.9
121162	0.18		4.3
121163	0.16		4.4
121164	0.21		3.9
121165	0.15		2.3
121166	0.47		2.9
121167	0.33		7.4
121168	0.29		4.8
121169	0.13		2.6
121170	0.20	0.18	3.4
121171	0.11		2.4
121172	0.07		2.7
*0211	2.13		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3374-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 27**
Attn: **Sue Deane**

Oct-03-08

We hereby certify the following assay of 22 core samples submitted Sep-18-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121173	0.08	0.08	2.0
121174	0.37		2.5
121175	0.01		<0.1
121176	0.14		3.4
121177	0.29		5.1
121178	0.42		3.7
121179	0.23		4.6
121180	0.16		3.6
121181	0.31		4.6
121182	0.16	0.14	5.6
121183	0.22		5.1
121184	0.18		6.9
121185	0.06		5.8
121186	0.15		4.9
121187	0.20		5.0
121188	0.16		6.6
121189	0.43		5.2
121190	0.32		4.6
121191	0.26		4.7
121192	0.23	0.23	4.1
121193	0.52		4.4
121194	0.16		4.8
*0211	2.24		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3374-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 27**
Attn: **Sue Deane**

Oct-03-08

We hereby certify the following assay of 22 core samples submitted Sep-18-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121195	0.20	0.17	5.7
121196	0.21		4.0
121197	0.48		7.4
121198	0.46		12.8
121199	0.13		5.9
121200	6.34		3.3
121201	0.34		4.8
121202	0.39		4.0
121203	0.46		3.6
121204	0.49	0.43	4.2
121205	0.22		3.3
121206	0.27		2.5
121207	0.94		3.5
121208	0.20		3.7
121209	0.33		3.7
121210	0.28		3.6
121211	0.40		6.1
121212	0.44		4.8
121213	0.33		9.0
121214	0.35	0.31	5.7
121215	0.25		5.8
121216	0.60		3.6
*0211	2.18		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3374-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 27**
Attn: **Sue Deane**

Oct-03-08

We hereby certify the following assay of 22 core samples submitted Sep-18-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121217	0.65	0.69	2.0
121218	0.29		2.1
121219	0.32		10.9
121220	0.34		6.0
121221	0.19		3.0
121222	0.01		0.5
121223	0.02		0.6
121224	<0.01		0.6
121225	<0.01		<0.1
121226	0.02	0.01	0.4
121227	0.01		1.0
121228	0.02		0.3
121229	<0.01		0.2
121230	0.01		0.2
121231	0.01		0.5
121232	0.02		1.2
121233	0.07		9.6
121234	0.08		3.2
121235	0.09		4.5
121236	0.11	0.10	9.6
121237	0.02		0.7
121238	0.15		1.6
*0211	2.05		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3374-RA7

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 27**
Attn: **Sue Deane**

Oct-03-08

We hereby certify the following assay of 22 core samples submitted Sep-18-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121239	0.02	0.04	0.9
121240	0.02		0.9
121241	0.10		1.1
121242	0.11		2.0
121243	0.08		2.1
121244	0.06		6.9
121245	0.23		4.6
121246	0.08		4.0
121247	0.21		4.2
121248	0.29	0.30	11.7
121249	0.01		0.3
121250	0.01		<0.1
121251	0.02		0.5
121252	0.01		0.4
121253	0.01		0.4
121254	0.02		0.2
121255	0.01		0.2
121256	0.01		0.5
121257	0.02		0.5
121258	0.02	0.01	0.3
121259	0.02		0.3
121260	0.01		0.3
*0211	2.18		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3374-RA8

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 27**
Attn: **Sue Deane**

Oct-03-08

We hereby certify the following assay of 22 core samples submitted Sep-18-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121261	0.01	0.01	<0.1
121262	0.01		<0.1
121262A	0.02		<0.1
130009	0.01		<0.1
130010	<0.01		<0.1
130011	<0.01		<0.1
130012	<0.01		<0.1
130013	0.01		<0.1
130014	0.02		0.3
130015	0.02	0.03	0.1
130016	0.01		<0.1
130017	0.02		<0.1
130018	0.01		<0.1
130019	0.02		0.1
130020	<0.01		<0.1
130021	0.02		0.6
130022	0.04		1.2
130023	0.69		3.1
130024	0.63		2.7
130025	1.85	1.92	159
130026	0.52		3.6
130027	0.07		2.3
*0211	2.15		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3374-RA9

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 27**
Attn: **Sue Deane**

Oct-03-08

We hereby certify the following assay of 22 core samples submitted Sep-18-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %	Zn %
130028	0.12	0.14	2.5		
130029	0.05		1.5		
130030	0.05		2.1		
130031	0.04		0.8		
130032	0.06		0.5		
130033	0.10		4.5		
130034	0.10		2.8		
130035	0.08		2.8		
130036	0.19		6.7		
130037	0.06	0.04	0.7		
130038	0.16		84.2		
130039	0.15		5.1		
130040	2.22		8.5		
130041	1.10		9.9		
130042	0.11		2.0		
130043	0.66		2.8		
130044	0.24		1.5		
130045	3.07		16.9		
130046	0.34		2.9		
130047	1.71	1.74	45.9	1.37	2.70
130048	0.56		10.3		
130049	0.67		3.8		
*0211	2.12				
*CCu-1c				0.35	3.94
*BLANK	<0.01			<0.01	<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3374-RA10

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 27**
Attn: **Sue Deane**

Oct-03-08

We hereby certify the following assay of 22 core samples submitted Sep-18-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne	Zn %
130050	0.01	0.01	<0.1		
130051	0.40		4.8		
130052	0.72		4.3		
130053	0.41		4.3		
130054	0.24		2.8		
130055	0.18		0.4		
130056	0.51		1.2		
130057	0.05		0.3		
130058	0.17		1.7		
130059	0.98	1.08	2.0		
130060	0.15		0.9		
130061	0.19		1.2		
130062	10.96		>200	304.0	1.23
PB0826	0.02		0.3		
PB0827	0.07		1.8		
PB0829	0.01		<0.1		
PB0830	0.02		<0.1		
PB0831	0.04		<0.1		
PB0832	0.01		<0.1		
WDR0812	1.07	1.14	64.7		
WDR0813	0.80		2.3		
WDR0814	4.88		10.7		
*0211	2.18				
*CCu-1c				1.28	3.98
*BLANK	<0.01			<0.1	<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3374-RA11

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 27**
Attn: **Sue Deane**

Oct-03-08

We hereby certify the following assay of 5 core samples submitted Sep-18-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
WDR0815	0.31	0.33	2.5	
WDR0816	0.34		7.8	
RS159	0.01		<0.1	
RS108A	7.32		28.3	1.47
*0211	2.11			
*CCu-1c				3.95
*BLANK	<0.01			<0.01

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3374RJ**

Date : Oct-03-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 27

Sample type: CORE

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121108	4.0	0.59	434	225	<0.5	<5	4.05	12	12	36	147	3.64	<1	0.31	<10	0.56	2441	17	0.01	9	928	41	1.29	16	2	178	<5	<0.01	<10	11	22	<10	139	1
121109	2.5	0.96	343	89	<0.5	<5	4.13	9	12	25	115	3.28	<1	0.31	<10	0.71	2200	10	0.01	6	1009	20	0.80	6	2	111	<5	<0.01	<10	<10	28	<10	147	1
121110	3.7	1.64	86	121	<0.5	<5	4.33	3	20	19	216	5.06	<1	0.23	<10	1.12	2330	35	0.01	8	1192	15	0.77	<5	6	158	<5	<0.01	<10	13	86	<10	222	2
121111	2.9	0.89	57	512	<0.5	<5	10.66	2	15	19	149	3.84	<1	0.26	<10	0.78	3435	77	0.01	4	1033	42	0.71	5	4	435	<5	<0.01	<10	14	44	<10	193	1
121112	1.0	2.02	16	177	<0.5	<5	3.90	<1	13	29	35	5.04	<1	0.23	<10	1.04	1644	5	0.09	3	1378	37	2.49	<5	6	91	<5	0.01	<10	<10	80	<10	137	2
121113	0.6	1.37	10	91	0.6	<5	6.76	<1	12	24	33	4.04	<1	0.24	<10	0.82	1591	<2	0.02	3	1122	71	2.34	<5	4	176	<5	<0.01	<10	<10	40	<10	113	2
121114	<0.2	1.21	<5	2515	<0.5	<5	3.62	<1	11	41	24	2.06	<1	0.26	17	0.78	597	<2	0.04	7	694	40	0.20	<5	2	222	<5	<0.01	<10	<10	27	<10	55	4
121115	0.4	1.76	10	158	<0.5	<5	4.41	<1	13	25	24	4.78	<1	0.29	<10	0.98	1208	<2	0.02	3	1297	25	2.63	<5	3	94	<5	<0.01	<10	<10	33	<10	110	2
121116	0.4	1.95	8	113	<0.5	<5	4.20	<1	19	33	20	6.44	<1	0.27	<10	1.11	1320	<2	0.02	2	1533	33	4.61	<5	3	96	<5	0.01	<10	12	37	<10	138	3
121117	0.3	1.94	8	135	<0.5	<5	3.81	<1	15	31	12	5.93	<1	0.24	<10	1.10	1285	<2	0.02	2	1519	13	3.67	<5	3	88	<5	0.01	<10	11	39	<10	153	3
121118	0.3	1.85	12	124	<0.5	<5	4.78	<1	14	26	9	5.59	<1	0.19	<10	1.16	1514	<2	0.02	2	1553	14	3.52	<5	4	138	<5	<0.01	<10	11	42	<10	70	2
121119	0.5	1.32	10	113	<0.5	<5	7.34	<1	12	46	8	4.70	<1	0.18	<10	0.91	1894	<2	0.02	3	1172	17	3.12	<5	4	239	<5	<0.01	<10	<10	33	<10	79	2
121120	0.5	1.80	6	140	<0.5	<5	4.52	<1	15	28	10	5.58	<1	0.24	<10	1.16	1623	<2	0.02	2	1508	13	3.79	<5	4	102	<5	0.01	<10	11	49	<10	93	3
121121	0.3	1.72	7	138	<0.5	<5	4.55	<1	14	24	13	5.12	<1	0.21	<10	1.08	1566	<2	0.02	2	1443	11	3.21	<5	3	125	<5	<0.01	<10	10	42	<10	90	3
121122	0.4	1.78	7	156	<0.5	<5	4.16	<1	15	21	14	5.72	<1	0.24	<10	1.20	1641	<2	0.02	2	1530	11	3.30	<5	5	122	<5	<0.01	<10	11	45	<10	86	3
121123	0.5	1.41	17	146	<0.5	<5	5.27	<1	14	25	20	5.25	<1	0.24	<10	0.92	1680	<2	0.02	2	1413	25	3.45	<5	5	135	<5	<0.01	<10	<10	34	<10	107	2
121124	0.4	1.51	7	159	<0.5	<5	4.86	<1	14	17	18	5.15	<1	0.27	<10	1.19	1820	<2	0.02	2	1380	9	2.98	<5	5	124	<5	<0.01	<10	<10	36	<10	99	2
121125	<0.2	0.98	<5	261	<0.5	<5	0.59	<1	8	121	1	2.09	<1	0.49	<10	0.56	604	<2	0.07	7	729	3	0.01	<5	2	51	<5	0.13	<10	<10	41	<10	51	2
121126	0.5	0.66	19	128	<0.5	<5	5.45	<1	16	22	8	5.84	<1	0.27	<10	1.15	1936	<2	0.01	2	1491	21	4.47	<5	5	140	<5	<0.01	<10	11	21	<10	92	3
121127	0.8	0.40	40	117	<0.5	<5	5.65	1	12	38	10	4.71	<1	0.24	<10	0.95	1739	<2	0.01	2	1187	45	3.84	<5	5	217	<5	<0.01	<10	10	12	<10	75	2
121128	2.5	0.30	52	101	<0.5	<5	9.31	3	14	31	32	4.78	<1	0.19	<10	0.50	1898	9	0.01	3	1179	55	4.28	<5	4	469	<5	<0.01	<10	11	8	<10	275	2
121129	1.3	0.62	31	106	<0.5	<5	4.32	1	13	22	30	4.06	<1	0.19	<10	0.74	1448	3	0.01	3	1094	21	3.03	<5	4	110	<5	<0.01	<10	<10	13	<10	102	2
121130	5.6	0.35	229	75	<0.5	<5	2.17	7	8	43	30	2.62	<1	0.20	<10	0.13	451	7	0.01	2	723	211	2.59	<5	1	68	<5	<0.01	<10	<10	7	<10	393	1
121131	73.6	0.38	252	95	<0.5	<5	2.08	8	9	43	50	2.79	<1	0.19	<10	0.14	394	2	0.01	3	872	241	2.62	26	1	76	<5	<0.01	<10	<10	8	<10	496	2
121132	0.6	0.76	<5	190	<0.5	<5	2.03	<1	6	42	3	1.62	<1	0.20	17	0.54	332	<2	0.03	6	805	27	0.07	<5	2	75	<5	<0.01	<10	<10	19	<10	52	8
121133	1.6	1.28	155	137	<0.5	<5	0.70	3	13	25	34	3.69	<1	0.25	<10	0.78	817	<2	0.01	3	1198	11	1.27	<5	2	33	<5	<0.01	<10	<10	32	<10	106	2
121134	3.1	1.17	219	79	<0.5	<5	1.11	6	19	39	110	4.91	<1	0.21	<10	0.70	768	10	0.01	5	1050	138	3.22	<5	2	47	<5	<0.01	<10	<10	41	<10	344	2
121135	1.4	1.51	98	125	<0.5	<5	1.39	2	14	18	56	4.05	<1	0.25	11	0.91	1065	3	0.01	3	1232	17	1.11	<5	2	59	<5	<0.01	<10	<10	38	<10	120	2
121136	1.4	1.22	54	117	<0.5	<5	2.17	1	11	38	83	3.37	<1	0.24	<10	0.63	968	5	0.01	3	1129	17	0.95	<5	2	99	<5	<0.01	<10	<10	30	<10	140	2
121137	1.3	1.72	24	125	<0.5	<5	3.27	1	13	14	72	4.19	<1	0.25	11	0.98	1550	4	0.02	3	1293	13	0.59	<5	3	149	<5	0.01	<10	<10	43	<10	134	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3374RJ**

Date : Oct-03-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 27

Sample type: CORE

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121138	0.9	1.53	19	124	<0.5	<5	3.56	<1	11	15	57	3.92	<1	0.26	10	0.83	1362	2	0.02	2	1215	15	0.87	<5	2	160	<5	0.01	<10	<10	41	<10	123	2
121139	0.6	1.60	33	112	<0.5	<5	3.40	1	12	11	46	3.83	<1	0.23	10	0.90	1395	3	0.02	2	1165	11	0.47	<5	2	170	<5	0.01	<10	<10	46	<10	106	2
121140	0.8	1.60	37	139	<0.5	<5	4.02	1	12	12	45	3.89	<1	0.27	11	0.85	1598	3	0.02	3	1226	12	0.65	<5	2	200	<5	0.01	<10	<10	40	<10	130	2
121141	1.4	1.31	39	127	<0.5	<5	4.62	1	10	14	95	3.55	<1	0.25	<10	0.69	1695	9	0.01	2	1065	13	1.17	<5	2	202	<5	0.01	<10	<10	31	<10	123	2
121142	1.4	0.97	88	96	<0.5	<5	2.19	2	13	25	55	3.86	<1	0.25	<10	0.52	903	5	0.01	3	1114	16	2.52	<5	2	101	<5	<0.01	<10	<10	23	<10	122	2
121143	1.4	0.69	127	88	<0.5	<5	0.86	3	12	33	26	3.78	<1	0.25	12	0.29	453	2	0.01	3	1039	17	3.11	<5	1	42	<5	<0.01	<10	<10	18	<10	96	2
121144	3.1	0.52	221	65	<0.5	<5	0.45	5	13	43	14	4.26	<1	0.26	<10	0.16	251	2	0.01	4	1114	68	4.19	<5	1	28	<5	<0.01	<10	<10	12	<10	158	2
121145	3.1	0.71	139	90	<0.5	<5	0.43	3	12	34	50	3.80	<1	0.25	<10	0.27	413	2	0.01	3	1102	71	3.03	<5	1	25	<5	<0.01	<10	<10	15	<10	176	2
121146	5.0	0.79	400	107	<0.5	<5	0.41	13	12	26	51	3.24	<1	0.25	<10	0.31	498	4	0.01	3	1104	191	2.01	<5	1	24	<5	<0.01	<10	<10	17	10	689	2
121147	2.4	0.83	140	124	<0.5	<5	0.37	3	11	26	31	2.71	<1	0.29	<10	0.30	537	4	0.01	3	1099	29	1.27	<5	1	21	<5	<0.01	<10	<10	18	<10	130	1
121148	5.3	0.49	481	89	<0.5	<5	0.50	16	9	52	55	3.25	<1	0.26	<10	0.12	286	5	0.01	4	992	355	2.81	<5	1	24	<5	<0.01	<10	<10	11	11	755	2
121149	8.9	0.21	1279	66	<0.5	<5	0.62	33	7	62	37	3.81	<1	0.16	<10	0.03	177	3	0.01	4	517	260	3.81	13	<1	29	<5	<0.01	<10	<10	4	10	673	2
121150	>200.0	0.52	523	153	<0.5	52	0.49	18	6	19	7314	1.98	6	0.14	<10	0.50	244	485	0.03	4	425	807	1.01	1446	1	65	<5	0.05	<10	<10	15	<10	835	2
121150A	>200.0	0.19	1478	11	<0.5	6	0.18	319	17	78	981	6.40	9	0.16	<10	0.02	143	4	0.01	4	464	>10000	>5.00	124	<1	8	<5	<0.01	<10	11	4	435	>10000	3
121151	69.6	0.38	1185	30	<0.5	5	0.21	87	14	80	121	7.27	3	0.24	<10	0.09	206	<2	0.01	6	796	864	>5.00	25	1	10	<5	<0.01	<10	13	8	104	7025	3
121152	8.5	0.83	296	149	<0.5	<5	0.30	9	13	38	33	3.52	<1	0.34	<10	0.27	555	2	0.01	4	1404	185	2.29	<5	1	10	<5	<0.01	<10	<10	14	<10	366	2
121153	6.1	0.86	541	108	<0.5	<5	0.25	13	12	46	27	4.34	<1	0.34	<10	0.25	506	5	0.01	4	1177	157	3.19	<5	1	9	<5	<0.01	<10	<10	15	<10	344	2
121154	25.2	0.56	1731	32	<0.5	5	0.31	46	13	90	66	8.26	1	0.26	<10	0.18	429	3	0.01	5	819	538	>5.00	7	1	12	<5	<0.01	<10	14	11	21	1427	4
121155	17.8	0.82	1417	43	<0.5	<5	0.36	34	14	51	30	7.49	1	0.31	<10	0.32	592	4	0.01	6	1187	383	>5.00	10	1	14	<5	<0.01	<10	<10	16	13	836	3
121156	4.2	0.77	455	75	<0.5	<5	0.34	11	15	39	12	5.26	<1	0.32	<10	0.30	525	14	0.01	5	1337	83	4.64	<5	1	12	<5	<0.01	<10	<10	15	<10	238	2
121157	87.6	0.71	595	89	<0.5	<5	0.27	19	13	43	91	5.17	<1	0.27	<10	0.28	527	16	0.01	4	1140	711	4.37	43	1	12	<5	<0.01	<10	<10	15	18	1284	2
121158	11.4	0.62	1697	95	<0.5	<5	0.37	43	12	47	31	4.28	<1	0.28	<10	0.19	413	8	0.01	3	1126	513	3.68	21	1	23	<5	<0.01	<10	<10	13	<10	626	2
121159	3.8	1.01	518	117	<0.5	<5	0.28	12	12	33	26	3.55	<1	0.32	<10	0.38	670	14	0.01	3	1307	53	1.63	<5	1	14	<5	<0.01	<10	<10	21	<10	205	2
121160	2.8	0.66	922	97	<0.5	<5	0.33	20	11	50	17	3.52	<1	0.27	<10	0.23	431	4	0.01	3	1106	60	2.53	7	1	18	<5	<0.01	<10	<10	14	<10	114	2
121161	3.9	0.43	405	79	<0.5	<5	0.51	10	12	60	128	3.93	<1	0.27	<10	0.11	287	57	0.01	4	1158	62	3.77	<5	1	28	<5	<0.01	<10	<10	9	<10	163	2
121162	4.3	1.03	123	112	<0.5	<5	0.68	3	16	30	209	4.26	<1	0.31	<10	0.47	869	58	0.01	3	1419	43	2.04	<5	2	30	<5	<0.01	<10	<10	24	<10	179	2
121163	4.4	1.05	300	158	<0.5	<5	0.53	7	13	39	172	4.29	<1	0.33	<10	0.47	874	64	0.01	4	1419	43	1.93	<5	2	28	<5	<0.01	<10	<10	24	<10	182	2
121164	3.9	1.06	169	122	<0.5	<5	0.67	5	14	24	156	4.08	<1	0.33	<10	0.51	923	133	0.01	3	1474	78	1.43	<5	2	30	<5	<0.01	<10	<10	26	<10	302	2
121165	2.3	1.32	81	117	<0.5	<5	3.13	2	14	20	111	4.93	<1	0.33	<10	0.84	1860	34	0.02	3	1653	48	1.27	<5	2	117	<5	<0.01	<10	<10	34	<10	192	2
121166	2.9	1.07	200	117	<0.5	<5	3.03	5	11	27	127	3.78	<1	0.32	<10	0.61	1851	25	0.02	3	1344	40	0.92	<5	2	124	<5	<0.01	<10	10	25	<10	202	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3374RJ**

Date : Oct-03-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 27

Sample type: CORE

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121167	7.4	0.47	71	109	<0.5	<5	2.60	3	13	29	183	4.36	<1	0.33	<10	0.86	1973	48	0.02	2	1328	41	0.75	5	3	108	<5	<0.01	<10	12	16	<10	263	1
121168	4.8	0.44	27	99	<0.5	<5	2.07	2	11	24	124	3.97	<1	0.31	10	0.83	1681	30	0.01	2	1261	36	0.38	<5	2	93	<5	<0.01	<10	10	14	<10	163	1
121169	2.6	0.41	88	105	<0.5	<5	0.61	3	14	33	119	4.28	<1	0.32	<10	0.46	872	53	0.01	3	1486	95	1.84	<5	2	28	<5	<0.01	<10	<10	14	<10	240	2
121170	3.4	0.44	341	77	<0.5	<5	0.56	8	12	52	59	4.58	<1	0.33	<10	0.22	401	24	0.01	4	1208	99	4.10	<5	2	20	<5	<0.01	<10	<10	12	<10	132	2
121171	2.4	0.37	168	114	<0.5	<5	1.04	7	14	33	32	4.49	<1	0.29	<10	0.49	986	8	0.01	3	1518	50	2.42	<5	2	40	<5	<0.01	<10	<10	13	<10	182	2
121172	2.7	0.39	118	110	<0.5	<5	0.74	12	15	31	50	4.73	<1	0.32	<10	0.47	1085	9	0.01	3	1566	45	2.08	<5	2	25	<5	<0.01	<10	<10	13	<10	462	2
121173	2.0	0.45	159	131	0.5	<5	1.80	6	14	31	33	4.35	<1	0.38	10	0.64	1556	3	0.01	3	1507	38	1.52	<5	3	70	<5	<0.01	<10	<10	15	<10	223	2
121174	2.5	0.39	217	108	0.5	<5	1.10	5	17	33	73	4.91	<1	0.33	<10	0.55	1082	11	0.01	4	1282	47	2.29	<5	3	45	<5	<0.01	<10	<10	17	<10	204	2
121175	<0.2	0.94	<5	234	<0.5	<5	0.51	<1	8	130	<1	2.05	<1	0.48	<10	0.57	554	<2	0.07	7	831	4	0.01	<5	2	49	<5	0.14	<10	<10	38	<10	48	2
121176	3.4	0.36	208	96	0.6	<5	2.43	5	23	27	82	6.18	<1	0.30	<10	1.08	1739	8	0.01	6	1006	74	1.92	<5	5	135	<5	<0.01	<10	11	26	<10	163	2
121177	5.1	0.42	265	111	0.5	<5	2.25	6	20	45	144	5.78	<1	0.33	<10	0.98	1665	47	0.01	6	1183	58	2.45	<5	4	127	<5	<0.01	<10	10	24	<10	183	2
121178	3.7	1.10	436	130	<0.5	<5	0.84	10	25	23	139	6.95	<1	0.30	<10	1.34	1169	9	0.01	5	1433	91	2.94	<5	4	38	<5	<0.01	<10	10	50	<10	207	3
121179	4.6	1.66	277	150	<0.5	<5	0.51	7	29	17	169	6.81	<1	0.35	<10	1.39	1134	10	0.01	6	1604	69	2.61	<5	4	19	<5	<0.01	<10	<10	66	<10	249	3
121180	3.6	1.43	234	152	<0.5	<5	0.99	6	20	28	110	5.63	<1	0.34	<10	1.16	1051	13	0.01	4	1402	48	2.48	<5	3	45	<5	<0.01	<10	<10	48	<10	208	3
121181	4.6	0.72	433	120	<0.5	<5	0.78	11	12	49	59	3.93	<1	0.27	<10	0.54	613	16	0.01	4	966	102	2.45	<5	2	35	<5	<0.01	<10	<10	22	<10	366	2
121182	5.6	1.60	172	157	<0.5	<5	0.43	4	24	22	145	5.88	<1	0.36	<10	0.99	1074	21	0.01	4	1432	48	2.28	<5	3	16	<5	<0.01	<10	<10	58	<10	260	2
121183	5.1	1.14	322	125	<0.5	<5	0.52	7	23	31	152	5.89	<1	0.34	<10	0.68	782	20	0.01	5	1415	48	3.69	<5	3	21	<5	<0.01	<10	<10	40	<10	183	2
121184	6.9	1.27	232	131	<0.5	<5	0.77	6	25	27	200	6.15	<1	0.34	<10	0.91	1067	23	0.01	5	1387	59	3.17	<5	3	40	<5	<0.01	<10	<10	46	<10	293	2
121185	5.8	1.86	149	138	<0.5	<5	1.11	4	25	17	208	6.95	<1	0.32	<10	1.48	1544	12	0.01	5	1451	65	2.64	<5	4	57	<5	<0.01	<10	11	70	<10	185	3
121186	4.9	2.40	289	154	<0.5	<5	1.20	7	26	18	145	7.64	<1	0.30	<10	1.86	1837	5	0.01	5	1582	82	2.93	<5	4	53	<5	<0.01	<10	13	89	<10	214	3
121187	5.0	1.90	103	157	<0.5	<5	0.62	3	26	16	196	6.38	<1	0.34	<10	1.52	1464	11	0.01	6	1685	70	1.68	<5	4	30	<5	<0.01	<10	<10	71	<10	228	2
121188	6.6	0.68	1138	47	<0.5	7	1.49	26	27	25	111	10.35	<1	0.35	<10	1.02	1105	11	0.01	6	1539	103	>5.00	<5	4	109	<5	<0.01	<10	21	30	<10	194	4
121189	5.2	1.44	817	83	<0.5	<5	0.56	20	25	21	164	7.34	<1	0.34	<10	1.01	940	7	0.01	6	1462	43	>5.00	<5	3	26	<5	<0.01	<10	11	56	<10	352	3
121190	4.6	2.22	206	174	<0.5	<5	0.58	7	26	17	229	6.63	<1	0.32	<10	1.53	1389	32	0.01	5	1563	45	1.71	<5	4	25	<5	<0.01	<10	<10	97	<10	322	3
121191	4.7	2.25	178	158	<0.5	<5	0.45	5	26	16	234	6.95	<1	0.34	<10	1.57	1196	43	0.01	6	1555	44	2.36	<5	4	21	<5	<0.01	<10	10	94	<10	277	3
121192	4.1	2.50	99	142	<0.5	<5	0.43	3	26	15	184	6.89	<1	0.31	<10	1.69	1248	22	0.01	6	1591	43	1.54	<5	4	23	<5	<0.01	<10	<10	106	<10	288	3
121193	4.4	2.49	257	168	<0.5	<5	0.51	7	27	15	359	6.89	<1	0.31	<10	1.69	1337	32	0.01	6	1620	34	1.55	<5	3	20	<5	<0.01	<10	11	97	<10	303	3
121194	4.8	1.63	174	150	<0.5	<5	0.60	5	25	15	296	6.04	<1	0.38	<10	1.00	887	37	0.01	4	1663	34	3.00	<5	3	27	<5	<0.01	<10	<10	57	<10	241	3
121195	5.7	1.41	166	126	<0.5	<5	0.68	4	25	9	359	6.31	<1	0.35	<10	1.11	1108	43	0.01	5	1460	45	3.25	<5	3	35	<5	<0.01	<10	<10	55	<10	284	3
121196	4.0	2.38	369	134	<0.5	<5	2.13	9	25	9	235	6.38	<1	0.35	<10	1.66	1900	21	0.01	4	1509	39	1.66	<5	4	116	<5	<0.01	<10	11	82	<10	250	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3374RJ**

Date : Oct-03-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 27

Sample type: CORE

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121197	7.4	1.83	533	122	<0.5	<5	0.49	13	31	8	309	6.98	<1	0.40	<10	0.89	993	34	0.01	5	1562	61	3.64	<5	4	27	<5	<0.01	<10	11	63	<10	330	3
121198	12.8	1.50	458	137	<0.5	<5	0.82	11	20	13	262	5.36	<1	0.34	<10	0.62	1002	26	0.01	4	1440	62	2.15	<5	3	45	<5	<0.01	<10	<10	45	<10	421	2
121199	5.9	1.57	232	116	<0.5	<5	2.14	5	21	13	165	5.63	<1	0.34	<10	0.70	1250	27	0.01	4	1484	31	2.41	<5	3	89	<5	<0.01	<10	<10	62	<10	185	3
121200	3.3	1.59	816	181	<0.5	17	9.65	18	54	80	505	6.55	14	0.20	13	0.37	1014	144	0.04	82	1134	97	2.57	<5	4	125	<5	0.14	<10	<10	47	54	100	19
121201	4.8	1.68	344	141	<0.5	<5	4.29	8	22	21	208	5.89	<1	0.37	<10	0.66	1587	28	0.02	5	1524	46	2.40	<5	5	122	<5	<0.01	<10	<10	63	<10	204	2
121202	4.0	1.21	597	141	<0.5	<5	4.33	14	22	15	181	5.70	<1	0.38	<10	0.62	1550	94	0.02	5	1540	43	3.59	<5	4	128	<5	<0.01	<10	<10	44	<10	255	2
121203	3.6	1.24	241	160	<0.5	<5	4.45	5	22	41	164	5.89	<1	0.43	<10	0.42	1440	25	0.02	6	1261	40	3.25	<5	3	133	<5	0.03	<10	<10	44	<10	181	2
121204	4.2	1.39	271	126	<0.5	<5	3.59	6	25	17	234	6.48	<1	0.40	<10	0.43	1212	60	0.01	7	1744	45	4.11	<5	4	127	<5	<0.01	<10	<10	47	<10	236	3
121205	3.3	2.03	73	134	<0.5	<5	4.91	2	25	14	304	6.48	<1	0.39	<10	0.74	1608	38	0.01	5	1804	34	1.55	<5	5	156	<5	0.01	<10	10	74	<10	214	3
121206	2.5	2.17	66	134	<0.5	<5	4.62	2	24	9	202	6.57	<1	0.36	<10	0.88	1456	28	0.01	6	1861	40	1.52	<5	5	155	<5	0.01	<10	10	71	<10	232	3
121207	3.5	1.66	207	137	<0.5	<5	4.37	5	22	12	205	5.47	<1	0.39	<10	0.60	1182	77	0.01	8	1712	83	1.86	<5	4	157	<5	<0.01	<10	10	66	<10	123	2
121208	3.7	1.94	445	137	<0.5	<5	4.06	11	21	8	169	6.04	<1	0.37	<10	0.77	1623	22	0.01	7	1768	29	1.73	<5	4	137	<5	<0.01	<10	10	56	<10	323	3
121209	3.7	1.78	562	131	<0.5	<5	3.97	13	25	10	164	6.04	<1	0.38	<10	0.70	1504	31	0.01	8	1802	41	2.25	<5	4	145	<5	<0.01	<10	<10	64	<10	298	3
121210	3.6	1.72	291	116	<0.5	<5	4.99	6	22	9	165	5.69	<1	0.38	<10	0.73	1546	18	0.01	6	1665	36	2.56	<5	4	139	<5	<0.01	<10	10	65	<10	175	3
121211	6.1	2.11	273	134	<0.5	<5	4.43	11	20	13	192	6.18	<1	0.36	<10	0.81	1776	11	0.01	6	1394	651	1.65	<5	3	155	<5	<0.01	<10	13	69	13	746	2
121212	4.8	1.84	851	129	<0.5	<5	7.38	22	23	9	148	5.78	<1	0.37	<10	0.67	2558	14	0.01	6	1425	100	1.66	<5	4	235	<5	<0.01	<10	15	90	10	616	2
121213	9.0	1.78	517	141	<0.5	<5	4.75	14	24	17	158	5.69	<1	0.40	<10	0.70	1750	7	0.01	6	1483	114	2.04	<5	4	146	<5	<0.01	<10	10	62	<10	365	2
121214	5.7	1.63	836	153	<0.5	<5	4.76	22	26	10	178	5.87	<1	0.42	<10	0.67	1942	8	0.01	8	1629	49	2.14	<5	5	170	<5	<0.01	<10	15	70	<10	311	2
121215	5.8	1.03	322	130	<0.5	<5	3.85	16	19	17	75	5.15	<1	0.37	<10	0.43	1362	3	0.01	4	1374	84	3.74	<5	3	138	<5	<0.01	<10	<10	34	<10	496	2
121216	3.6	0.97	955	118	<0.5	<5	5.52	23	21	12	66	5.23	<1	0.40	<10	0.42	1483	3	0.01	4	1466	56	4.15	<5	3	225	<5	<0.01	<10	<10	48	<10	180	2
121217	2.0	0.99	963	108	<0.5	<5	5.73	22	19	11	26	5.14	<1	0.43	<10	0.48	1704	2	0.01	3	1441	49	4.39	<5	3	269	<5	0.01	<10	<10	35	<10	106	2
121218	2.1	0.80	1233	111	<0.5	<5	6.32	28	16	8	48	4.63	<1	0.41	<10	0.48	1971	9	0.01	2	1439	51	3.51	<5	3	280	<5	<0.01	<10	13	22	<10	160	2
121219	10.9	0.75	284	88	<0.5	<5	9.94	10	12	20	87	3.84	<1	0.28	<10	0.49	2468	67	0.01	2	877	549	2.88	<5	2	361	<5	<0.01	<10	14	32	11	728	1
121220	6.0	1.82	707	123	<0.5	<5	4.64	17	24	10	207	6.00	<1	0.41	<10	1.02	2153	38	0.01	3	1419	141	2.35	<5	4	221	<5	<0.01	<10	15	73	<10	304	2
121221	3.0	1.88	95	92	<0.5	<5	3.97	2	20	10	114	5.68	<1	0.36	<10	1.00	1777	37	0.02	3	1377	28	1.59	<5	4	168	<5	0.01	<10	10	76	12	137	2
121222	0.5	1.66	35	158	<0.5	<5	4.04	1	15	14	100	4.22	<1	0.31	<10	0.88	1137	17	0.05	1	1413	25	1.95	<5	5	77	<5	0.01	<10	<10	53	<10	104	2
121223	0.6	2.01	28	139	<0.5	<5	4.31	<1	16	18	119	4.35	<1	0.30	10	1.17	1268	3	0.09	2	1439	58	1.86	<5	6	91	<5	0.01	<10	<10	64	<10	74	2
121224	0.6	1.50	19	136	<0.5	<5	4.94	<1	13	11	14	5.20	<1	0.29	<10	0.95	1602	<2	0.03	1	1540	48	3.27	<5	4	99	<5	<0.01	<10	<10	57	<10	127	2
121225	<0.2	1.04	<5	242	<0.5	<5	0.61	<1	8	87	1	2.19	<1	0.53	<10	0.61	597	<2	0.08	5	893	4	0.01	<5	2	53	<5	0.14	<10	<10	40	<10	53	2
121226	0.4	1.50	21	97	<0.5	<5	4.61	<1	13	15	31	4.93	<1	0.20	<10	0.99	1513	<2	0.02	1	1461	27	2.86	<5	4	121	<5	<0.01	<10	<10	43	<10	97	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3374RJ**

Date : Oct-03-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 27

Sample type: CORE

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121227	1.0	1.89	34	119	<0.5	<5	3.63	1	16	22	123	5.53	<1	0.25	<10	1.34	1271	2	0.04	2	1636	54	3.12	<5	4	66	<5	0.01	<10	<10	64	<10	135	3
121228	0.3	1.89	<5	118	<0.5	<5	3.88	1	13	10	16	5.45	<1	0.21	<10	1.29	1329	<2	0.02	1	1592	65	2.97	<5	3	85	<5	0.01	<10	<10	51	<10	230	2
121229	0.2	2.13	6	124	<0.5	<5	4.16	<1	15	16	10	6.14	<1	0.20	13	1.38	1378	<2	0.02	2	1596	14	3.05	<5	3	86	<5	0.01	<10	<10	47	<10	77	3
121230	0.2	2.37	13	156	<0.5	<5	4.53	<1	14	9	15	5.95	<1	0.26	11	1.41	1468	<2	0.02	1	1674	17	2.27	<5	4	105	<5	0.01	<10	<10	48	<10	69	3
121231	0.5	2.34	14	183	<0.5	<5	2.97	<1	15	10	25	6.13	<1	0.31	<10	1.39	1369	<2	0.02	2	1789	18	2.31	<5	4	72	<5	0.01	<10	<10	53	<10	75	3
121232	1.2	2.49	53	111	0.6	<5	2.73	1	18	13	54	7.39	<1	0.42	<10	1.50	1396	<2	0.02	2	1725	41	3.71	<5	5	62	<5	<0.01	<10	10	62	<10	104	3
121233	9.6	0.74	63	166	<0.5	<5	11.57	15	8	18	162	2.94	<1	0.24	<10	0.35	2175	3	0.01	2	770	1660	2.45	<5	1	229	<5	<0.01	<10	12	16	27	1815	1
121234	3.2	1.02	51	136	<0.5	<5	10.91	9	9	14	73	3.08	<1	0.24	<10	0.54	2277	<2	0.01	2	897	478	1.73	<5	2	252	<5	<0.01	<10	13	20	15	1013	1
121235	4.5	0.65	242	124	<0.5	<5	3.08	13	12	51	176	4.33	<1	0.30	<10	0.21	628	3	0.01	3	1135	368	4.03	<5	1	130	<5	<0.01	<10	<10	12	17	1134	2
121236	9.6	0.43	649	127	<0.5	<5	2.29	24	9	43	308	3.42	<1	0.28	<10	0.10	402	3	0.01	3	866	681	3.50	26	1	77	<5	<0.01	<10	<10	9	21	1448	2
121237	0.7	1.68	24	170	<0.5	<5	3.39	<1	13	20	38	4.86	<1	0.30	<10	0.95	1543	2	0.02	3	1389	17	2.01	<5	3	104	<5	<0.01	<10	<10	41	<10	106	2
121238	1.6	0.97	128	112	<0.5	<5	2.17	5	17	31	51	5.02	<1	0.31	<10	0.45	812	3	0.01	4	1594	256	3.97	<5	2	103	<5	<0.01	<10	<10	21	<10	361	2
121239	0.9	1.01	51	126	<0.5	<5	2.36	1	15	31	43	4.67	<1	0.31	<10	0.49	815	<2	0.01	3	1452	23	3.32	<5	2	107	<5	<0.01	<10	<10	21	<10	143	2
121240	0.9	1.80	26	150	<0.5	<5	1.65	<1	14	15	48	4.98	<1	0.29	12	1.02	1317	<2	0.02	3	1422	10	1.46	<5	3	66	<5	<0.01	<10	<10	40	<10	118	2
121241	1.1	0.76	93	227	<0.5	<5	1.89	2	14	23	62	4.85	<1	0.34	11	0.95	1382	<2	0.02	3	1443	15	1.27	<5	2	134	<5	<0.01	<10	<10	23	<10	112	2
121242	2.0	0.62	24	213	<0.5	<5	2.41	<1	13	23	179	4.70	<1	0.36	11	0.89	1551	6	0.02	3	1399	15	0.77	<5	2	137	<5	<0.01	<10	<10	27	<10	99	2
121243	2.1	1.16	59	198	<0.5	<5	1.42	1	17	24	123	4.77	<1	0.42	11	0.79	1188	4	0.01	3	1547	23	0.97	<5	2	78	<5	<0.01	<10	<10	31	<10	123	2
121244	6.9	0.74	104	121	<0.5	<5	2.53	2	13	42	78	4.25	<1	0.30	<10	0.45	939	3	0.01	3	1272	24	2.34	<5	2	159	<5	<0.01	<10	<10	18	<10	127	2
121245	4.6	0.65	238	132	<0.5	<5	0.41	8	14	25	96	4.16	<1	0.34	<10	0.34	522	3	0.01	3	1293	161	2.58	<5	1	30	<5	<0.01	<10	<10	15	<10	456	2
121246	4.0	0.88	213	166	<0.5	<5	0.41	5	13	25	82	3.94	<1	0.36	10	0.54	911	2	0.01	3	1297	17	1.19	<5	2	27	<5	<0.01	<10	<10	22	<10	242	2
121247	4.2	0.48	657	175	<0.5	<5	0.62	18	10	29	78	2.84	<1	0.36	10	0.15	350	<2	0.01	2	1293	294	1.91	<5	1	31	<5	<0.01	<10	<10	11	<10	435	1
121248	11.7	0.40	413	108	<0.5	<5	0.53	13	12	46	92	3.75	<1	0.31	<10	0.23	296	<2	0.01	4	1119	215	2.90	<5	1	45	<5	<0.01	<10	<10	10	10	656	2
121249	0.3	1.97	15	207	<0.5	<5	3.71	<1	10	21	12	4.69	<1	0.23	<10	1.43	1622	<2	0.03	1	1401	18	1.27	<5	5	73	<5	<0.01	<10	<10	60	<10	110	2
121250	<0.2	0.98	<5	235	<0.5	<5	0.53	<1	9	135	<1	2.26	<1	0.51	<10	0.61	575	<2	0.08	7	890	2	0.01	<5	2	51	5	0.15	<10	<10	39	<10	49	2
121251	0.5	1.53	18	92	<0.5	<5	5.40	<1	14	17	17	5.13	<1	0.20	<10	1.18	1742	<2	0.02	1	1421	18	2.77	<5	3	182	<5	<0.01	<10	<10	32	<10	102	2
121252	0.4	1.74	17	127	<0.5	<5	3.44	<1	12	21	13	5.68	<1	0.20	<10	1.13	1585	<2	0.04	2	1651	18	3.37	<5	3	62	<5	<0.01	<10	<10	34	<10	103	3
121253	0.4	2.16	9	137	<0.5	<5	3.73	<1	12	15	13	5.24	<1	0.21	<10	1.66	1871	<2	0.03	1	1482	19	1.96	<5	4	59	<5	0.01	<10	<10	59	<10	133	2
121254	0.2	1.76	16	125	<0.5	<5	5.19	<1	12	18	15	4.96	<1	0.19	<10	1.20	1647	2	0.02	1	1467	10	2.36	<5	3	75	<5	0.01	<10	<10	39	<10	108	2
121255	0.2	1.89	9	109	<0.5	<5	4.75	<1	11	15	13	4.89	<1	0.16	<10	1.21	1574	<2	0.02	1	1462	10	1.90	<5	3	68	<5	0.01	<10	<10	35	<10	98	2
121256	0.5	1.74	16	123	<0.5	<5	5.03	<1	15	20	41	5.09	<1	0.20	<10	1.11	1588	2	0.01	2	1413	20	2.05	<5	3	99	<5	<0.01	<10	<10	40	<10	82	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3374RJ**

Date : Oct-03-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 27

Sample type: CORE

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121257	0.5	1.58	21	108	<0.5	<5	3.85	<1	16	23	23	5.92	<1	0.20	<10	1.00	1190	2	0.01	2	1583	25	3.77	<5	3	83	<5	<0.01	<10	<10	27	<10	82	3
121258	0.3	1.76	16	114	<0.5	<5	5.11	<1	13	25	13	5.57	<1	0.17	<10	1.17	1488	<2	0.01	2	1587	8	3.08	<5	3	114	<5	0.01	<10	10	33	<10	94	2
121259	0.3	2.09	16	168	<0.5	<5	2.41	<1	14	18	9	5.72	<1	0.18	<10	1.44	1398	<2	0.02	1	1665	26	2.03	<5	4	48	<5	<0.01	<10	<10	53	<10	165	2
121260	0.3	1.74	29	69	<0.5	<5	4.36	<1	13	24	9	5.58	<1	0.20	<10	1.18	1528	<2	0.02	2	1617	14	3.15	<5	3	99	<5	0.01	<10	<10	42	<10	83	2
121261	<0.2	1.99	6	110	<0.5	<5	4.20	<1	15	17	14	5.20	<1	0.19	17	1.30	1681	<2	0.01	2	1667	16	3.06	<5	4	119	<5	0.04	<10	<10	49	<10	105	3
121262	<0.2	1.93	12	100	<0.5	<5	5.29	<1	16	19	16	5.71	<1	0.17	16	1.31	1928	<2	0.01	2	1636	15	3.69	<5	3	154	<5	0.04	<10	<10	41	<10	88	3
121262A	<0.2	2.18	5	130	<0.5	<5	3.33	<1	15	16	29	5.44	<1	0.18	13	1.47	1721	<2	0.02	2	1709	12	2.65	<5	4	97	<5	0.07	<10	<10	48	<10	84	3
130009	<0.2	2.75	11	107	<0.5	<5	3.01	<1	14	16	22	5.70	<1	0.15	13	1.77	1869	2	0.01	2	1777	7	1.03	<5	3	91	<5	0.01	<10	<10	52	<10	130	2
130010	<0.2	2.80	8	128	<0.5	<5	4.09	<1	14	16	20	5.19	<1	0.15	12	1.80	2127	<2	0.02	2	1826	6	0.19	<5	3	119	<5	0.01	<10	10	57	<10	139	2
130011	<0.2	2.75	17	98	<0.5	<5	4.58	<1	13	12	19	5.27	<1	0.16	18	1.74	2257	<2	0.01	2	1901	4	0.45	<5	4	154	<5	0.01	<10	<10	56	<10	112	2
130012	<0.2	2.09	20	151	<0.5	<5	4.22	1	15	19	23	5.55	<1	0.18	19	1.27	2004	<2	0.01	3	1760	17	2.07	<5	3	130	<5	0.01	<10	<10	38	<10	197	2
130013	<0.2	2.62	19	98	<0.5	<5	3.56	<1	15	10	26	5.62	<1	0.18	17	1.68	2182	2	0.01	2	1805	9	0.89	<5	3	109	<5	0.01	<10	<10	49	<10	122	2
130014	0.3	1.44	44	104	<0.5	<5	1.85	2	14	26	47	4.70	<1	0.18	14	0.75	1357	<2	0.01	2	1461	50	2.39	<5	2	78	<5	0.01	<10	<10	33	<10	188	2
130015	<0.2	1.92	32	98	<0.5	<5	2.46	<1	15	17	21	6.56	<1	0.15	<10	1.00	1859	<2	0.01	1	1431	57	3.18	<5	3	80	<5	0.03	<10	10	46	<10	102	3
130016	<0.2	2.18	25	124	<0.5	<5	3.10	<1	14	36	20	6.20	<1	0.18	<10	1.04	2182	<2	0.01	2	1408	31	2.10	<5	3	88	<5	0.05	<10	<10	54	<10	109	3
130017	<0.2	2.78	9	118	<0.5	<5	3.14	<1	12	14	20	6.89	<1	0.19	11	1.38	2479	<2	0.01	1	1947	8	1.46	<5	3	99	<5	0.10	<10	18	61	<10	121	3
130018	<0.2	2.07	27	118	<0.5	<5	4.98	<1	22	20	25	5.88	<1	0.22	<10	1.14	2064	<2	0.01	3	1861	11	2.27	<5	5	160	<5	0.02	<10	<10	62	<10	104	2
130019	<0.2	1.96	29	112	<0.5	<5	4.26	<1	20	17	25	6.01	<1	0.20	13	1.14	1948	<2	0.01	3	1741	12	2.90	<5	5	148	<5	0.01	<10	<10	56	<10	113	2
130020	<0.2	1.98	39	119	<0.5	<5	3.68	1	20	20	23	5.24	<1	0.22	<10	1.17	1810	<2	0.01	3	1609	8	1.93	<5	5	118	<5	0.04	<10	<10	57	<10	116	2
130021	0.6	1.20	141	99	<0.5	<5	5.63	3	17	21	13	5.25	<1	0.20	<10	0.75	1956	<2	0.01	3	1369	24	3.72	<5	4	197	<5	0.02	<10	<10	34	<10	88	2
130022	1.2	1.47	169	97	<0.5	<5	4.90	3	19	19	16	6.05	<1	0.18	<10	0.90	1807	<2	0.01	3	1448	25	4.28	<5	3	158	<5	0.01	<10	<10	37	<10	123	2
130023	3.1	1.18	151	152	<0.5	<5	0.83	4	17	16	54	4.61	<1	0.24	<10	0.47	1450	<2	0.01	4	943	87	2.46	<5	2	58	<5	<0.01	<10	<10	18	<10	184	2
130024	2.7	1.52	77	187	<0.5	<5	0.55	2	13	14	57	4.22	<1	0.25	<10	0.56	1679	<2	0.01	3	959	18	1.06	<5	2	33	<5	0.01	<10	<10	23	<10	138	2
130025	159.4	0.92	221	213	<0.5	<5	5.42	6	17	24	3876	3.76	5	0.20	<10	0.19	708	74	0.03	33	673	211	1.35	204	2	192	<5	0.08	<10	<10	25	24	236	11
130026	3.6	0.79	128	154	<0.5	<5	0.92	3	13	19	51	3.40	<1	0.24	<10	0.26	985	2	0.01	3	860	70	2.14	<5	1	74	<5	<0.01	<10	<10	9	<10	181	2
130027	2.3	1.21	107	169	<0.5	<5	0.66	3	12	23	19	3.72	<1	0.26	<10	0.52	1187	3	0.01	4	1158	84	1.56	<5	1	42	<5	<0.01	<10	<10	24	<10	176	2
130028	2.5	1.22	107	194	<0.5	<5	0.47	16	12	28	35	3.86	<1	0.28	<10	0.52	1095	<2	0.01	2	1055	385	1.78	<5	1	31	<5	<0.01	<10	<10	23	20	1357	2
130029	1.5	1.12	95	191	<0.5	<5	0.52	4	11	24	10	3.50	<1	0.30	<10	0.46	932	<2	0.01	2	1077	192	1.50	<5	1	34	<5	<0.01	<10	<10	23	<10	366	2
130030	2.1	1.09	77	153	<0.5	<5	0.44	6	12	18	20	4.12	<1	0.31	<10	0.47	681	<2	0.01	2	1136	257	2.33	<5	1	25	<5	<0.01	<10	<10	22	<10	497	2
130031	0.8	1.07	100	148	<0.5	<5	0.51	4	15	15	13	4.19	<1	0.34	<10	0.47	685	<2	0.01	3	1242	116	2.46	<5	1	33	<5	<0.01	<10	<10	19	<10	334	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3374RJ**

Date : Oct-03-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 27

Sample type: CORE

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130032	0.5	0.88	115	144	<0.5	<5	0.52	3	14	17	7	3.78	<1	0.32	<10	0.34	578	<2	0.01	3	1208	42	2.55	<5	1	36	<5	<0.01	<10	<10	15	<10	82	2
130033	4.5	0.63	152	119	<0.5	<5	1.54	12	14	25	15	4.26	1	0.29	<10	0.20	766	<2	0.01	3	1042	599	3.66	<5	1	125	<5	<0.01	<10	<10	11	17	1147	2
130034	2.8	0.68	176	124	<0.5	<5	1.37	4	14	24	26	3.77	<1	0.28	<10	0.23	868	4	0.01	3	1010	38	2.91	<5	1	73	<5	<0.01	<10	<10	13	<10	101	2
130035	2.8	0.89	60	176	<0.5	<5	0.58	2	13	18	14	3.30	<1	0.26	<10	0.39	691	2	0.01	3	1079	63	1.62	<5	1	34	<5	<0.01	<10	<10	19	<10	118	2
130036	6.7	0.65	326	89	<0.5	<5	1.47	7	15	16	10	4.16	<1	0.29	<10	0.22	494	2	0.01	3	1179	61	3.66	<5	1	48	<5	<0.01	<10	<10	10	<10	77	2
130037	0.7	0.48	107	88	<0.5	<5	1.92	2	16	17	2	4.64	<1	0.29	<10	0.14	909	4	0.01	3	1354	31	4.71	<5	1	139	<5	<0.01	<10	<10	8	<10	43	2
130038	84.2	0.60	140	111	<0.5	<5	4.65	4	9	44	12	3.92	<1	0.27	<10	0.21	2555	2	0.01	2	821	254	3.50	12	1	390	<5	<0.01	<10	15	9	<10	172	1
130039	5.1	0.77	187	109	<0.5	<5	6.59	4	9	25	9	3.06	<1	0.28	<10	0.30	2341	<2	0.01	2	1034	54	1.89	<5	2	340	<5	<0.01	<10	11	16	<10	123	1
130040	8.5	0.44	308	149	<0.5	<5	7.37	20	9	30	48	3.23	<1	0.22	<10	0.15	2252	2	0.01	2	792	513	3.08	<5	2	223	<5	<0.01	<10	<10	9	28	1845	1
130041	9.9	0.75	407	108	<0.5	<5	1.31	22	10	23	31	3.77	<1	0.26	<10	0.28	852	2	0.01	2	943	436	2.78	<5	1	92	<5	<0.01	<10	<10	17	27	1811	2
130042	2.0	1.47	216	117	<0.5	<5	3.44	11	21	11	63	5.11	<1	0.29	<10	0.65	2058	4	0.01	2	1360	354	2.47	<5	3	210	<5	0.01	<10	10	37	15	947	2
130043	2.8	1.34	412	81	<0.5	<5	5.70	12	19	18	132	4.66	<1	0.26	<10	0.78	2430	6	0.01	2	1100	428	2.69	<5	3	233	<5	0.01	<10	<10	41	<10	415	2
130044	1.5	1.63	236	93	<0.5	<5	3.82	6	24	15	158	5.12	<1	0.26	<10	0.99	1910	16	0.01	3	1441	87	2.42	<5	3	151	<5	0.02	<10	<10	53	<10	226	2
130045	16.9	1.09	440	99	<0.5	<5	5.63	99	15	27	295	4.72	1	0.22	<10	0.50	2726	<2	0.01	3	870	4880	3.23	<5	2	160	<5	0.01	<10	17	47	115	7463	2
130046	2.9	0.54	543	66	<0.5	<5	13.22	39	8	32	145	2.61	<1	0.14	10	0.26	5621	<2	0.01	2	429	124	1.90	<5	1	376	<5	<0.01	<10	27	18	40	2563	<1
130047	45.9	1.45	421	60	<0.5	<5	11.82	332	8	56	987	6.00	2	0.07	<10	1.34	4178	<2	0.01	19	182	>10000	>5.00	19	1	320	<5	<0.01	<10	26	39	437	>10000	2
130048	10.3	0.15	376	74	<0.5	<5	9.68	19	13	27	553	4.16	<1	0.11	<10	0.04	2719	10	0.01	2	649	301	4.57	<5	1	262	<5	<0.01	<10	10	4	17	1141	1
130049	3.8	1.40	229	80	<0.5	<5	6.09	8	22	17	269	4.65	<1	0.26	<10	0.64	1790	49	0.01	3	1104	191	2.09	<5	4	173	<5	0.02	<10	<10	47	<10	405	2
130050	<0.2	0.85	<5	256	<0.5	<5	0.35	<1	8	91	1	2.03	<1	0.47	<10	0.56	552	<2	0.05	6	795	27	0.01	<5	2	39	<5	0.14	<10	<10	38	<10	80	2
130051	4.8	1.21	303	99	<0.5	<5	3.22	8	27	17	325	4.83	<1	0.31	<10	0.49	1231	13	0.01	4	1196	106	2.80	<5	2	101	<5	<0.01	<10	<10	38	<10	193	2
130052	4.3	1.53	105	193	<0.5	<5	3.48	3	20	12	224	4.60	<1	0.30	<10	0.69	1399	24	0.01	2	1419	73	1.18	<5	3	157	<5	<0.01	<10	<10	40	<10	174	2
130053	4.3	1.61	73	89	<0.5	<5	2.83	2	20	9	214	4.60	<1	0.29	<10	0.72	1093	20	0.01	2	1425	166	1.33	<5	3	84	<5	<0.01	<10	<10	47	<10	201	2
130054	2.8	0.73	168	59	<0.5	<5	8.54	5	12	23	26	2.70	<1	0.19	<10	0.36	3257	11	0.01	2	798	76	1.65	<5	1	190	<5	<0.01	<10	16	20	<10	156	<1
130055	0.4	1.54	140	163	<0.5	<5	2.10	4	25	11	64	4.71	<1	0.30	<10	0.53	836	10	0.01	2	1499	97	1.28	<5	3	76	<5	<0.01	<10	<10	60	<10	267	2
130056	1.2	2.33	97	124	<0.5	<5	3.57	7	26	8	81	6.47	<1	0.32	<10	0.99	1324	6	0.01	3	1631	98	1.24	<5	4	118	<5	0.01	<10	<10	76	11	605	3
130057	0.3	2.61	36	117	<0.5	<5	4.22	<1	27	3	145	6.19	<1	0.26	<10	1.59	1676	2	0.02	4	1405	16	0.56	<5	5	162	<5	0.14	<10	11	87	<10	122	3
130058	1.7	1.18	219	93	<0.5	<5	9.65	14	15	14	101	3.70	<1	0.25	10	0.59	3878	<2	0.01	3	824	47	1.69	<5	2	218	<5	0.02	<10	20	39	18	1148	1
130059	2.0	0.59	615	55	<0.5	<5	1.55	15	20	14	27	5.21	<1	0.29	<10	0.19	573	<2	0.01	2	1177	88	4.78	<5	2	56	<5	0.02	<10	<10	25	<10	185	2
130060	0.9	1.93	185	143	<0.5	<5	3.72	5	24	7	83	5.73	<1	0.38	<10	0.98	1719	<2	0.02	2	1680	21	2.23	<5	4	106	<5	0.04	<10	<10	49	<10	144	3
130061	1.2	2.05	85	98	<0.5	<5	4.87	1	21	6	43	4.89	<1	0.29	<10	1.14	1874	<2	0.02	2	1408	38	0.80	<5	3	146	<5	0.02	<10	<10	48	<10	61	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3374RJ**

Date : Oct-03-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 27

Sample type: CORE

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130062	>200.0	1.24	127	66	<0.5	<5	9.02	95	12	18	385	4.74	2	0.21	<10	0.65	2739	<2	0.01	2	842	3055	3.43	13	2	230	<5	0.01	<10	18	33	187	>10000	2
PB0826	0.3	3.40	<5	196	<0.5	<5	1.84	1	18	33	23	5.11	<1	0.25	<10	1.05	959	<2	0.21	3	1260	21	2.10	<5	11	112	<5	0.15	<10	<10	114	<10	113	4
PB0827	1.8	1.14	99	134	<0.5	<5	0.21	2	9	21	37	6.65	<1	0.35	<10	0.24	411	<2	0.01	5	1631	42	1.71	<5	3	17	<5	<0.01	<10	12	33	<10	79	3
PB0829	<0.2	2.47	44	168	<0.5	<5	3.02	1	28	90	42	5.79	<1	0.28	<10	2.01	1651	<2	0.04	15	1442	19	0.93	<5	19	86	<5	0.05	<10	<10	174	<10	143	4
PB0830	<0.2	2.71	52	133	<0.5	<5	1.87	1	28	96	94	7.17	<1	0.12	<10	2.51	1621	<2	0.01	17	1734	15	1.32	<5	17	62	<5	<0.01	<10	<10	197	<10	112	3
PB0831	<0.2	2.14	22	106	<0.5	<5	0.94	<1	11	14	13	4.99	<1	0.17	<10	0.93	634	2	0.07	3	1106	12	1.59	<5	4	35	<5	0.04	<10	<10	42	<10	87	4
PB0832	<0.2	1.31	18	92	<0.5	<5	3.64	<1	10	17	12	3.42	<1	0.14	<10	0.79	986	<2	0.02	2	1023	9	1.59	<5	2	77	<5	<0.01	<10	<10	21	<10	76	2
WDR0812	64.7	0.33	9723	71	<0.5	<5	0.06	224	7	43	36	4.12	<1	0.14	<10	0.10	264	3	0.01	2	615	795	2.17	96	1	3	<5	<0.01	<10	<10	12	14	934	2
WDR0813	2.3	0.32	1727	85	<0.5	<5	0.06	37	3	18	14	3.01	<1	0.27	<10	0.02	84	2	0.01	1	1120	50	0.87	26	1	3	<5	<0.01	<10	<10	5	<10	37	2
WDR0814	10.7	0.33	290	65	<0.5	<5	5.16	64	11	31	311	3.88	<1	0.11	<10	0.18	1927	7	0.01	3	794	3044	3.85	<5	2	84	<5	<0.01	<10	<10	20	96	6028	1
WDR0815	2.5	0.70	313	136	<0.5	<5	0.77	16	7	49	87	4.07	<1	0.22	<10	0.32	931	19	0.01	2	929	387	0.76	<5	2	14	<5	0.07	<10	<10	29	17	1073	3
WDR0816	7.8	1.56	493	27	<0.5	6	0.15	93	10	29	92	12.64	5	0.16	<10	1.03	1287	<2	0.01	1	952	2945	>5.00	<5	2	7	<5	<0.01	<10	28	47	156	9871	6
RS159	<0.2	2.19	6	54	<0.5	<5	3.20	<1	19	9	50	5.09	<1	0.20	10	1.42	2213	<2	0.01	3	1389	24	0.31	<5	4	157	<5	0.10	<10	<10	71	<10	102	2
RS108A	28.3	0.18	234	31	<0.5	<5	5.07	148	5	51	388	2.83	2	0.10	<10	0.07	1621	<2	0.01	2	306	5400	3.03	6	<1	156	<5	<0.01	<10	<10	4	242	>10000	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3395-RA1

Company: **Ascot Resources Ltd.**
 Project: **Dilworth/Shipment 28**
 Attn: **Sue Deane**

Oct-09-08

We hereby certify the following assay of 22 rock samples submitted Sep-23-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %	Zn %
121263	0.02	0.04	<0.1		
121264	0.01		<0.1		
121265	0.02		1.0		
121266	0.03		0.6		
121267	0.09		3.5		
121268	0.27		13.1		
121269	0.02		0.2		
121270	0.03		0.2		
121271	0.01		<0.1		
121272	0.06	0.06	<0.1		
121273	0.05		0.5		
121274	0.04		0.5		
121275	6.23		2.6		
121276	0.08		1.5		
121277	0.45		62.5	1.16	4.97
121278	1.00		65.6		1.83
121279	0.28		40.6		
121280	0.13		5.1		
121281	0.07		2.2		
121282	0.04	0.04	1.3		
121283	0.04		1.1		
121284	0.10		1.0		
*0211	2.16				
*CCu-1c				0.35	3.95
*BLANK	<0.01			<0.01	<0.01

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3395-RA2

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 28**
Attn: **Sue Deane**

Oct-09-08

We hereby certify the following assay of 22 rock samples submitted Sep-23-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121285	0.15	0.16	1.5
121286	0.17		2.0
121287	0.17		19.1
121288	0.13		26.3
121289	0.19		35.7
121290	0.07		23.6
121291	0.15		39.5
121292	0.14		39.8
121293	0.05		2.0
121294	0.13	0.14	11.5
121295	0.08		1.3
121296	0.03		1.1
121297	0.12		1.7
121298	0.21		2.9
121299	0.18		2.0
121300	0.01		<0.1
121301	0.23		1.9
121302	0.05		1.3
121303	0.06		3.1
121304	0.07	0.05	0.3
121305	0.08		2.1
121306	0.10		1.9
*0211	2.11		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3395-RA3

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 28**
Attn: **Sue Deane**

Oct-09-08

We hereby certify the following assay of 22 rock samples submitted Sep-23-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
121307	0.09	0.10	1.5	
121308	0.15		12.9	
121309	0.01		0.7	
121310	0.01		<0.1	
121311	0.10		10.8	
121312	0.02		0.4	
121313	0.02		2.3	
121314	0.01		0.4	
121315	0.01		0.3	
121316	0.04	0.03	1.5	
121317	0.08		2.2	
121318	0.03		0.8	
121319	0.02		0.8	
121320	0.02		0.9	
121321	0.02		0.2	
121322	0.03		1.0	
121323	0.06		2.2	
121324	0.08		2.1	
121325	<0.01		<0.1	
121326	0.62	0.65	17.5	1.41
121327	0.90		88.6	
121328	3.17		165	
*0211	2.18			
*CCu-1c				3.95
*BLANK	<0.01			<0.01

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3395-RA4

Company: **Ascot Resources Ltd.**
 Project: **Dilworth/Shipment 28**
 Attn: **Sue Deane**

Oct-09-08

We hereby certify the following assay of 22 rock samples submitted Sep-23-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag	Zn
121329	0.95	1.03	85.1		
121330	0.08		2.4		
121331	0.30		10.6		
121332	0.17		4.5		
121333	0.09		1.1		
121334	0.04		1.5		
121335	0.05		0.4		
121336	0.38		13.4		1.51
121337	0.04		0.6		
121338	0.02	0.02	<0.1		
121339	0.03		<0.1		
121340	0.02		0.3		
121341	0.03		0.5		
121342	0.08		0.8		
121343	0.15		2.8		
121344	0.07		0.6		
121345	0.14		2.7		
121346	0.18		3.3		
121347	0.05		0.8		
121348	0.05	0.03	0.4		
121349	0.02		0.3		
121350	0.12		>200	774.6	
*0211	2.21				
*CCu-1c				131.3	3.91
*BLANK	<0.01			<0.1	<0.01

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3395-RA5

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 28**
Attn: **Sue Deane**

Oct-09-08

We hereby certify the following assay of 22 rock samples submitted Sep-23-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121351	0.07	0.05	1.9
121352	0.04		0.4
121353	0.05		0.6
121354	0.02		<0.1
121355	0.05		0.3
121356	0.01		0.1
121357	0.02		<0.1
121358	0.07		2.1
121359	0.05		1.0
121360	0.04	0.04	0.6
121361	0.02		0.6
121362	0.05		<0.1
121363	0.10		0.9
121364	0.10		0.3
121365	0.13		1.6
121366	0.13		<0.1
121367	0.11		<0.1
121368	0.04		<0.1
121369	0.05		0.1
121370	0.07	0.09	<0.1
121371	0.14		<0.1
121372	0.31		<0.1
*0211	2.16		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3395-RA6

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 28**
Attn: **Sue Deane**

Oct-09-08

We hereby certify the following assay of 22 rock samples submitted Sep-23-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121373	0.36	0.31	1.3
121374	0.12		1.4
121375	<0.01		<0.1
121376	0.04		0.5
121377	0.04		0.5
121378	0.02		0.2
121379	0.01		0.2
121380	0.05		0.9
121381	0.02		1.0
121382	0.02	0.01	0.6
121383	0.02		0.6
121384	0.03		0.2
121385	0.01		<0.1
121386	0.01		0.2
121387	0.02		0.3
121388	0.04		<0.1
121389	0.02		<0.1
121390	0.01		<0.1
121391	0.01		<0.1
121392	0.04	0.05	<0.1
130063	3.20		19.3
130064	0.09		4.0
*0211	2.14		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3395-RA7

Company: **Ascot Resources Ltd.**
 Project: **Dilworth/Shipment 28**
 Attn: **Sue Deane**

Oct-09-08

We hereby certify the following assay of 22 rock samples submitted Sep-23-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
130065	0.18	0.13	2.0	
130066	0.24		3.6	
130067	0.24		2.3	
130068	0.33		3.4	
130069	0.08		1.4	
130070	0.05		0.7	
130071	0.27		2.3	
130072	0.20		1.7	
130073	0.27		3.3	
130074	0.26	0.25	3.8	
130075	0.12		>200	797.4
130076	0.32		6.3	
130077	0.43		5.4	
130078	0.38		10.8	
130079	0.19		6.6	
130080	0.22		5.7	
130081	0.16		3.0	
130082	0.43		4.9	
130083	0.49		4.0	
130084	0.25	0.26	2.9	
130085	0.41		2.4	
130086	0.51		2.3	
*0211	2.14			
*CCu-1c				131.6
*BLANK	<0.01			<0.1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3395-RA8

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 28**
Attn: **Sue Deane**

Oct-09-08

We hereby certify the following assay of 22 rock samples submitted Sep-23-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130087	0.52	0.53	1.9
130088	0.22		0.9
130089	0.11		0.6
130090	0.30		1.9
130091	0.14		1.2
130092	0.04		0.4
130093	0.06		0.8
130094	0.18		0.7
130095	0.10		0.7
130096	0.48	0.47	5.9
130097	0.55		1.4
130098	0.04		1.0
130099	0.25		6.0
130100	<0.01		<0.1
130101	0.06		4.1
130102	0.04		0.3
130103	0.11		0.5
130104	0.49		4.3
130105	0.04		0.8
130106	0.05	0.04	0.2
130107	0.16		1.0
130108	0.01		<0.1
*0211	2.14		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3395-RA9

Company: **Ascot Resources Ltd.**
Project: **Dilworth/Shipment 28**
Attn: **Sue Deane**

Oct-09-08

We hereby certify the following assay of 5 rock samples submitted Sep-23-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
130109	0.02	0.02	<0.1	
130110	0.02		<0.1	
130111	0.02		<0.1	
WDR08-10	1.23		127	
WDR08-11	146.0		>200	2271
*0211	2.21			
*CCu-1c				131.6
*BLANK	<0.01			<0.1

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3395RJ**

Date : Oct-09-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth/Shipment 28

Sample type: Rock

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121263	<0.2	1.71	6	102	<0.5	<5	3.61	<1	13	38	24	4.66	<1	0.15	10	1.24	1553	<2	0.01	9	1431	12	2.36	<5	3	115	<5	0.03	<10	<10	38	<10	69	2
121264	<0.2	1.81	7	110	<0.5	<5	3.23	<1	16	24	10	5.34	<1	0.19	12	1.37	1507	<2	0.01	10	1583	29	3.14	<5	3	101	<5	0.02	<10	<10	45	<10	101	3
121265	1.0	1.27	36	129	<0.5	<5	4.74	2	13	33	87	4.27	<1	0.17	<10	0.86	1566	<2	0.01	4	1381	177	2.90	<5	2	118	<5	<0.01	<10	<10	29	<10	270	2
121266	0.6	0.74	50	105	<0.5	<5	4.22	3	10	43	42	3.20	<1	0.17	<10	0.44	1256	2	0.01	5	998	139	2.49	<5	1	91	<5	<0.01	<10	<10	17	<10	322	1
121267	3.5	0.41	155	82	<0.5	<5	4.41	6	10	44	90	3.46	<1	0.14	<10	0.21	1032	3	0.01	4	937	145	3.42	<5	1	118	<5	<0.01	<10	<10	9	<10	537	1
121268	13.1	0.56	150	93	<0.5	<5	7.66	11	12	48	88	4.23	<1	0.17	<10	0.34	1629	<2	0.01	5	1049	538	3.70	<5	2	391	<5	<0.01	<10	<10	11	19	1206	2
121269	0.2	1.83	27	96	<0.5	<5	3.80	<1	16	15	33	4.82	<1	0.19	<10	1.21	1630	4	0.01	3	1426	12	1.42	<5	3	129	<5	<0.01	<10	<10	39	<10	97	2
121270	0.2	1.45	27	92	<0.5	<5	4.33	<1	13	25	40	4.08	<1	0.19	<10	0.78	1156	7	0.01	3	1409	32	1.48	<5	2	245	<5	<0.01	<10	<10	33	<10	67	2
121271	<0.2	1.75	34	114	<0.5	<5	5.32	<1	16	25	79	4.41	<1	0.13	<10	0.98	1955	2	0.07	5	1190	10	0.56	<5	4	136	<5	0.02	<10	<10	66	<10	67	2
121272	<0.2	1.77	15	102	<0.5	<5	4.42	<1	13	19	41	4.12	<1	0.17	<10	1.05	1695	6	0.03	4	1320	16	0.57	<5	3	141	<5	0.01	<10	<10	52	<10	83	2
121273	0.5	1.61	39	101	<0.5	<5	3.42	1	13	20	64	4.08	<1	0.18	<10	1.01	1213	8	0.01	3	1412	17	1.24	<5	2	162	<5	<0.01	<10	<10	35	<10	109	2
121274	0.5	1.75	48	105	<0.5	<5	1.92	1	15	14	40	4.57	<1	0.20	<10	1.04	1181	4	0.01	3	1504	15	1.11	<5	2	79	<5	<0.01	<10	<10	43	<10	101	2
121275	2.6	1.45	768	140	<0.5	44	8.77	16	53	75	477	6.07	13	0.18	12	0.37	937	149	0.04	77	1070	91	2.37	<5	4	117	<5	0.13	<10	<10	45	54	95	17
121276	1.5	1.56	252	134	<0.5	<5	3.40	10	14	16	32	4.25	<1	0.23	<10	0.88	1644	<2	0.02	3	1383	73	1.40	<5	2	130	<5	<0.01	<10	<10	36	13	768	2
121277	62.5	0.32	631	22	<0.5	9	0.91	559	8	68	212	7.62	27	0.14	<10	0.11	382	<2	0.01	4	529	>10000	>5.00	44	<1	30	<5	<0.01	<10	11	8	873	>10000	3
121278	65.6	0.26	1355	36	<0.5	6	0.45	229	11	49	94	6.36	11	0.16	<10	0.06	169	2	0.01	4	846	8955	>5.00	74	1	24	<5	<0.01	<10	<10	6	331	>10000	3
121279	40.6	0.26	532	63	<0.5	<5	0.34	23	12	65	35	5.22	1	0.17	<10	0.04	75	2	0.01	5	868	257	>5.00	28	1	21	<5	<0.01	<10	<10	6	25	1613	3
121280	5.1	0.52	493	82	<0.5	<5	0.29	12	11	36	30	4.38	<1	0.19	<10	0.20	293	4	0.01	3	1026	118	3.83	9	1	21	<5	<0.01	<10	<10	12	<10	325	2
121281	2.2	0.82	217	111	<0.5	<5	0.53	6	16	39	58	3.87	<1	0.23	<10	0.35	575	6	0.01	4	1276	123	2.69	<5	1	42	<5	<0.01	<10	<10	22	<10	279	2
121282	1.3	1.62	44	117	<0.5	<5	0.51	1	16	17	65	4.44	<1	0.22	12	0.88	1271	3	0.01	3	1379	20	1.01	<5	2	37	<5	0.01	<10	<10	38	<10	118	2
121283	1.1	1.10	242	124	<0.5	<5	0.34	5	15	26	44	4.11	<1	0.24	<10	0.59	703	2	0.02	3	1404	21	2.38	<5	1	30	<5	<0.01	<10	<10	27	<10	120	2
121284	1.0	0.40	276	61	<0.5	<5	0.64	6	17	24	6	5.44	<1	0.20	<10	0.13	189	13	0.02	4	1512	44	>5.00	<5	1	56	<5	<0.01	<10	<10	12	<10	141	3
121285	1.5	0.53	445	54	<0.5	<5	0.59	9	23	18	20	6.64	<1	0.23	12	0.21	233	8	0.02	6	2165	73	>5.00	<5	1	47	<5	<0.01	<10	<10	13	<10	211	4
121286	2.0	0.43	450	49	<0.5	<5	0.56	9	23	5	23	7.21	<1	0.17	12	0.18	224	16	0.02	5	2082	72	>5.00	<5	1	41	<5	<0.01	<10	<10	11	<10	170	4
121287	19.1	0.48	441	52	<0.5	<5	0.67	9	23	25	207	7.35	<1	0.28	16	0.12	203	12	0.02	5	1895	54	>5.00	7	1	45	<5	<0.01	<10	<10	11	<10	144	5
121288	26.3	0.55	202	64	<0.5	<5	0.47	4	13	50	113	6.28	<1	0.24	11	0.20	295	9	0.02	4	1241	57	>5.00	11	1	40	<5	<0.01	<10	<10	9	<10	178	3
121289	35.7	0.69	170	74	<0.5	<5	0.53	4	14	77	94	5.93	<1	0.25	<10	0.27	435	8	0.02	4	1230	47	>5.00	22	1	42	<5	<0.01	<10	<10	10	<10	214	3
121290	23.6	1.06	360	111	<0.5	<5	0.50	8	17	35	82	5.50	<1	0.24	<10	0.50	697	6	0.02	4	1506	79	4.02	16	1	35	<5	0.01	<10	<10	25	<10	170	3
121291	39.5	0.94	317	139	<0.5	<5	0.50	9	13	56	73	4.00	<1	0.27	<10	0.41	557	5	0.02	4	1176	166	2.64	26	1	34	<5	<0.01	<10	<10	24	<10	368	2
121292	39.8	0.76	531	125	<0.5	<5	0.38	13	14	45	71	3.81	<1	0.24	<10	0.28	452	11	0.02	3	1188	160	2.71	33	1	29	<5	<0.01	<10	<10	18	<10	388	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

Ascot Resources Ltd.

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Report No : 8V3395RJ

Attention: Sue Deane

Tel: (604) 327-3436 Fax: (604) 327-3423

Date : Oct-09-08

Project: Dilworth/Shipment 28

Sample type: Rock

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121293	2.0	1.22	241	157	<0.5	<5	0.35	5	16	23	29	4.41	<1	0.26	11	0.56	797	4	0.03	3	1395	28	2.29	<5	2	28	<5	<0.01	<10	<10	29	<10	121	2
121294	11.5	1.55	93	157	<0.5	<5	0.31	4	19	34	65	5.07	<1	0.26	10	0.76	1054	10	0.03	4	1256	201	2.08	<5	2	24	<5	<0.01	<10	<10	44	<10	423	2
121295	1.3	1.28	295	126	<0.5	<5	0.35	6	15	22	28	4.57	<1	0.25	<10	0.56	949	11	0.02	3	1409	48	1.94	<5	1	21	<5	<0.01	<10	<10	30	<10	112	2
121296	1.1	1.41	72	144	<0.5	<5	0.35	1	16	20	34	3.89	<1	0.27	<10	0.64	848	14	0.03	3	1467	62	1.13	<5	2	23	<5	<0.01	<10	<10	23	<10	100	2
121297	1.7	0.51	161	105	<0.5	<5	0.32	6	14	43	42	3.97	<1	0.26	<10	0.12	189	25	0.02	4	1222	57	3.76	<5	1	27	<5	<0.01	<10	<10	10	<10	473	3
121298	2.9	0.48	521	97	<0.5	<5	0.50	11	14	39	55	4.39	<1	0.22	<10	0.13	262	49	0.02	3	1109	50	4.12	<5	1	37	<5	<0.01	<10	<10	8	<10	104	3
121299	2.0	1.09	206	144	<0.5	<5	0.34	4	17	27	78	4.50	<1	0.29	10	0.44	509	24	0.02	4	1369	45	2.78	<5	2	26	<5	<0.01	<10	<10	17	<10	110	3
121300	<0.2	0.97	<5	286	<0.5	<5	0.46	<1	9	131	<1	2.32	<1	0.52	<10	0.68	633	2	0.05	6	932	2	0.01	<5	2	41	<5	0.15	<10	<10	43	<10	58	2
121301	1.9	1.99	410	86	<0.5	<5	0.31	10	22	32	90	5.14	<1	0.17	<10	1.30	1523	8	0.01	4	1664	158	1.26	<5	2	9	<5	0.01	<10	<10	47	<10	368	2
121302	1.3	1.67	208	83	<0.5	<5	0.41	8	17	26	49	4.76	<1	0.16	<10	1.12	1201	4	0.01	4	1486	130	1.53	<5	2	11	<5	0.01	<10	<10	43	<10	400	2
121303	3.1	1.48	172	75	<0.5	<5	0.79	46	15	33	43	5.68	3	0.15	<10	0.95	1178	<2	0.02	3	1423	1213	3.20	<5	2	34	<5	0.01	<10	<10	43	90	5713	2
121304	0.3	1.71	143	87	<0.5	<5	0.62	3	19	22	30	5.32	<1	0.17	<10	1.09	1322	<2	0.01	2	1637	48	2.21	<5	2	21	<5	0.01	<10	<10	48	<10	180	2
121305	2.1	1.51	184	78	<0.5	<5	0.50	25	16	23	36	6.04	<1	0.15	<10	1.00	1184	<2	0.01	3	1532	855	3.52	<5	2	18	<5	<0.01	<10	<10	39	46	2900	2
121306	1.9	1.90	166	76	<0.5	<5	0.65	10	21	21	58	5.63	<1	0.16	<10	1.27	1357	<2	0.01	3	1747	136	2.04	<5	2	29	<5	0.01	<10	<10	46	12	758	2
121307	1.5	1.77	113	138	<0.5	<5	1.38	7	15	44	35	4.80	<1	0.29	<10	1.04	1134	6	0.02	4	1418	135	1.89	<5	2	56	<5	<0.01	<10	<10	42	12	686	2
121308	12.9	1.11	221	92	<0.5	<5	1.59	64	15	59	164	6.89	<1	0.25	<10	0.67	971	<2	0.02	10	1389	1551	4.75	<5	4	67	<5	0.01	<10	<10	44	85	5298	4
121309	0.7	1.55	40	274	<0.5	<5	2.55	8	18	25	29	4.13	<1	0.20	29	1.11	962	<2	0.06	18	2750	26	0.17	<5	6	121	<5	0.02	<10	<10	45	18	1141	4
121310	<0.2	0.91	39	89	<0.5	<5	3.54	1	16	15	17	4.03	<1	0.23	22	1.09	842	<2	0.02	8	2589	13	0.48	<5	5	142	<5	<0.01	<10	<10	24	<10	135	2
121311	10.8	1.48	161	97	<0.5	<5	0.48	10	26	18	64	5.99	<1	0.21	<10	0.95	915	<2	0.01	4	1633	394	3.17	<5	2	19	<5	<0.01	<10	<10	42	19	1013	2
121312	0.4	2.28	75	99	<0.5	<5	0.93	1	29	14	46	6.55	<1	0.20	<10	1.57	1531	<2	0.01	5	1864	16	1.47	<5	4	44	<5	<0.01	<10	<10	61	<10	183	3
121313	2.3	1.95	111	82	<0.5	<5	1.16	3	28	20	65	6.18	<1	0.17	<10	1.54	1473	<2	0.02	5	1717	81	2.10	<5	4	63	<5	<0.01	<10	<10	66	<10	205	3
121314	0.4	1.87	85	91	<0.5	<5	1.04	1	27	14	39	6.14	<1	0.15	<10	1.41	1324	<2	0.02	5	1771	25	2.65	<5	4	52	<5	0.01	<10	<10	70	21	125	3
121315	0.3	1.95	78	81	<0.5	<5	0.99	1	25	15	43	5.85	<1	0.15	<10	1.41	1264	<2	0.02	4	1726	14	1.99	<5	4	45	<5	0.01	<10	<10	69	<10	102	2
121316	1.5	1.70	185	99	<0.5	<5	0.56	3	27	16	54	6.02	<1	0.20	<10	1.13	986	<2	0.02	4	1720	16	2.86	<5	3	26	<5	<0.01	<10	<10	52	11	95	3
121317	2.2	1.90	176	97	<0.5	<5	0.61	3	28	16	50	6.28	<1	0.20	<10	1.38	1150	<2	0.01	5	1831	15	2.84	<5	3	32	<5	<0.01	<10	<10	54	<10	105	3
121318	0.8	1.85	146	96	<0.5	<5	0.81	2	28	17	15	6.43	<1	0.19	<10	1.46	1165	<2	0.01	4	1744	17	3.29	<5	3	47	<5	0.01	<10	<10	56	<10	115	3
121319	0.8	1.73	163	69	<0.5	<5	0.72	3	28	14	23	5.97	<1	0.15	<10	1.50	1132	<2	0.02	4	1749	15	2.80	<5	3	39	<5	<0.01	<10	<10	59	<10	131	2
121320	0.9	1.86	103	69	<0.5	<5	0.62	1	27	17	17	5.92	<1	0.14	<10	1.58	1230	<2	0.02	7	1785	13	2.40	<5	4	27	<5	<0.01	<10	<10	64	13	104	2
121321	0.2	1.95	72	61	<0.5	<5	1.06	1	27	14	21	5.74	<1	0.14	<10	1.56	1395	<2	0.02	4	1727	11	1.87	<5	4	52	<5	<0.01	<10	<10	66	17	91	2
121322	1.0	1.99	136	60	<0.5	<5	0.99	3	28	11	55	6.21	<1	0.15	<10	1.54	1535	<2	0.01	4	1763	41	2.08	<5	4	48	<5	<0.01	<10	10	59	<10	141	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3395RJ**

Date : Oct-09-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth/Shipment 28

Sample type: Rock

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121323	2.2	1.71	200	78	<0.5	<5	0.47	6	26	19	55	5.84	<1	0.16	<10	1.13	1327	<2	0.01	4	1484	202	2.51	<5	3	20	<5	<0.01	<10	<10	54	<10	325	2
121324	2.1	1.89	294	75	<0.5	<5	0.42	8	26	11	58	5.91	<1	0.19	<10	1.37	1376	<2	0.01	5	1658	89	2.49	<5	3	18	<5	<0.01	<10	10	55	11	471	3
121325	<0.2	0.90	<5	242	<0.5	<5	0.46	<1	9	90	<1	2.24	<1	0.45	<10	0.62	579	<2	0.05	5	860	2	0.01	<5	2	41	<5	0.14	<10	<10	41	<10	50	2
121326	17.5	0.34	1200	23	<0.5	12	0.28	147	10	55	229	14.34	4	0.11	<10	0.19	294	<2	0.01	2	664	3164	>5.00	<5	1	12	<5	<0.01	<10	26	15	264	>10000	6
121327	88.6	0.26	549	38	<0.5	5	0.87	65	8	69	100	8.26	3	0.10	<10	0.15	254	<2	0.01	3	606	1867	>5.00	7	<1	22	<5	<0.01	<10	10	9	109	6875	3
121328	165.7	0.16	547	28	<0.5	5	0.44	61	5	77	117	6.41	4	0.07	<10	0.08	160	2	<0.01	3	351	2966	>5.00	44	<1	16	<5	<0.01	<10	<10	5	99	6553	3
121329	85.1	0.58	278	36	<0.5	<5	0.85	32	11	96	100	5.70	2	0.08	<10	0.42	456	7	0.01	4	689	5089	>5.00	13	1	51	<5	<0.01	<10	<10	19	53	3524	3
121330	2.4	0.32	150	79	<0.5	<5	<0.01	11	15	66	20	0.34	<1	0.09	<10	0.24	778	<2	<0.01	2	893	235	3.18	10	2	67	<5	<0.01	<10	<10	34	<10	736	2
121331	10.6	<0.01	218	52	<0.5	5	<0.01	22	13	68	75	<0.01	<1	0.05	<10	0.08	552	4	<0.01	2	697	918	>5.00	15	1	71	<5	<0.01	<10	<10	19	28	2550	2
121332	4.5	1.34	223	51	<0.5	5	4.16	16	18	24	49	6.23	<1	0.13	<10	0.95	1352	3	0.01	1	1097	618	>5.00	14	2	214	<5	0.01	<10	<10	43	20	1666	3
121333	1.1	1.12	169	62	<0.5	<5	1.91	4	18	49	19	4.53	<1	0.13	<10	0.79	978	<2	0.01	2	1105	128	3.40	9	2	66	<5	<0.01	<10	<10	38	<10	281	2
121334	1.5	1.56	147	67	<0.5	<5	2.42	4	23	26	43	5.13	<1	0.15	<10	1.16	1335	<2	0.01	2	1207	159	3.42	10	3	90	<5	0.03	<10	<10	52	<10	405	3
121335	0.4	1.53	145	59	0.5	<5	3.34	3	20	17	28	4.97	<1	0.13	<10	1.08	1462	<2	0.01	1	1148	83	3.20	9	3	122	<5	0.06	<10	<10	53	<10	200	3
121336	13.4	0.95	309	51	<0.5	8	6.71	101	19	23	121	7.28	2	0.12	<10	0.70	2100	<2	0.01	<1	952	7234	>5.00	17	2	326	<5	0.04	<10	13	36	149	>10000	4
121337	0.6	1.79	124	56	0.7	<5	4.05	4	20	12	28	5.10	<1	0.12	<10	1.33	1777	<2	0.01	1	1250	229	2.83	10	3	145	<5	0.09	<10	<10	52	<10	462	3
121338	<0.2	2.24	55	60	0.6	<5	2.89	<1	20	14	25	5.06	<1	0.12	<10	1.61	1488	<2	0.01	1	1071	47	1.55	9	4	105	<5	0.08	<10	<10	65	<10	110	2
121339	<0.2	1.90	45	60	0.5	<5	3.18	<1	18	12	48	4.68	<1	0.12	<10	1.23	1318	<2	0.01	1	1088	33	1.69	8	4	126	<5	0.06	<10	<10	62	<10	106	3
121340	0.3	1.98	56	68	0.5	<5	3.43	1	19	15	57	5.51	<1	0.15	<10	1.29	1301	<2	0.01	1	1190	39	2.31	9	4	111	<5	0.05	<10	<10	64	<10	132	3
121341	0.5	2.12	63	56	0.7	<5	2.20	1	19	10	76	4.96	<1	0.12	<10	1.48	1207	<2	0.01	1	1131	49	1.47	9	4	77	<5	0.08	<10	<10	66	<10	125	3
121342	0.8	1.53	127	59	0.5	<5	1.56	2	18	18	40	4.73	<1	0.14	<10	0.96	821	<2	0.01	1	1097	56	2.58	9	3	53	<5	0.06	<10	<10	48	<10	159	3
121343	2.8	1.30	176	65	<0.5	<5	0.29	10	13	27	33	5.26	<1	0.15	<10	0.80	884	7	0.01	2	986	485	3.49	13	2	10	<5	0.01	<10	<10	35	12	1063	3
121344	0.6	1.60	116	71	<0.5	<5	0.75	5	16	18	58	4.38	<1	0.15	<10	1.00	1156	<2	0.01	3	1063	97	1.62	9	2	21	<5	<0.01	<10	<10	42	<10	436	2
121345	2.7	1.17	98	82	<0.5	<5	0.38	5	11	21	32	3.54	<1	0.16	<10	0.69	826	<2	0.01	1	910	261	1.68	8	1	16	<5	0.01	<10	<10	19	<10	485	2
121346	3.3	1.24	122	69	<0.5	<5	1.97	10	12	20	53	4.01	<1	0.16	<10	0.75	1020	<2	0.01	1	1097	213	2.30	7	1	122	<5	0.01	<10	<10	30	13	1182	2
121347	0.8	1.60	42	60	<0.5	<5	1.42	5	13	13	30	3.96	<1	0.14	<10	0.98	1182	<2	0.01	1	1165	261	1.12	7	2	72	<5	0.01	<10	<10	38	<10	579	2
121348	0.4	1.50	58	89	<0.5	<5	0.85	8	14	15	58	4.02	<1	0.16	<10	0.89	1088	<2	0.01	2	1241	65	1.04	7	2	32	<5	<0.01	<10	<10	34	12	884	2
121349	0.3	1.52	45	75	<0.5	<5	1.59	4	15	11	41	4.12	<1	0.14	<10	0.93	1105	<2	0.01	1	1182	36	1.12	7	2	64	<5	<0.01	<10	<10	36	<10	469	2
121350	>200.0	0.53	429	162	<0.5	116	0.47	15	6	18	6911	1.81	4	0.13	<10	0.48	241	458	0.03	4	420	836	1.02	1420	1	68	<5	0.04	<10	<10	19	<10	867	2
121351	1.9	0.93	113	84	<0.5	<5	0.56	10	12	50	67	3.95	<1	0.17	<10	0.52	601	<2	0.01	3	1231	116	2.01	<5	2	20	<5	<0.01	<10	<10	21	11	689	2
121352	0.4	0.64	132	63	<0.5	<5	0.38	4	16	26	25	4.79	<1	0.21	<10	0.28	278	4	0.01	2	1410	33	4.31	<5	1	12	<5	<0.01	<10	<10	14	<10	176	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3395RJ**

Date : Oct-09-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth/Shipment 28

Sample type: Rock

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121353	0.6	1.03	101	81	<0.5	<5	0.83	3	14	31	24	4.26	<1	0.16	<10	0.65	671	4	0.01	2	1230	54	2.42	<5	1	33	<5	<0.01	<10	<10	21	<10	201	2
121354	<0.2	1.16	41	669	<0.5	<5	3.20	<1	13	18	14	3.56	<1	0.21	21	0.99	682	<2	0.02	7	2302	12	0.45	<5	4	168	<5	<0.01	<10	<10	25	<10	104	2
121355	0.3	2.10	143	158	<0.5	<5	1.83	3	22	23	26	5.80	<1	0.18	<10	1.32	1284	<2	0.01	5	1817	19	1.53	<5	4	83	<5	<0.01	<10	<10	52	<10	197	3
121356	<0.2	2.23	101	148	<0.5	<5	2.15	1	21	13	29	5.58	<1	0.15	<10	1.51	1425	<2	0.02	4	1762	10	0.97	<5	4	91	<5	<0.01	<10	<10	62	<10	106	2
121357	<0.2	1.52	89	75	<0.5	<5	0.93	2	24	17	23	5.76	<1	0.15	<10	1.08	931	<2	0.02	4	1747	21	2.40	<5	3	45	<5	<0.01	<10	<10	48	<10	139	3
121358	2.1	1.65	184	84	<0.5	<5	0.68	3	22	17	43	5.81	<1	0.22	<10	0.97	865	<2	0.01	4	1683	25	2.82	<5	3	24	<5	<0.01	<10	<10	40	<10	67	3
121359	1.0	1.96	146	73	<0.5	<5	0.63	3	23	16	55	6.16	<1	0.19	<10	0.99	926	<2	0.01	4	1608	21	1.94	<5	3	21	<5	<0.01	<10	11	50	<10	129	3
121360	0.6	1.81	268	73	<0.5	<5	3.13	5	21	15	49	5.12	<1	0.18	<10	1.02	1195	<2	0.01	3	1615	19	1.78	<5	3	101	<5	<0.01	<10	<10	35	<10	130	2
121361	0.6	1.86	88	98	<0.5	<5	4.28	1	22	15	57	5.20	<1	0.19	<10	1.07	1369	<2	0.01	3	1572	15	1.98	<5	3	145	<5	<0.01	<10	<10	49	<10	80	2
121362	<0.2	2.09	133	124	<0.5	<5	4.82	2	25	14	18	5.66	<1	0.19	<10	1.10	1557	<2	0.01	4	1625	11	1.89	<5	4	178	<5	<0.01	<10	11	69	<10	99	3
121363	0.9	1.09	295	66	<0.5	<5	3.44	6	24	23	18	5.53	<1	0.18	<10	0.53	986	<2	0.01	4	1372	20	4.00	<5	2	123	<5	<0.01	<10	<10	32	<10	102	3
121364	0.3	0.67	91	77	<0.5	<5	7.82	8	6	26	27	2.61	<1	0.17	<10	0.45	2560	<2	0.01	1	751	177	1.40	<5	2	148	<5	<0.01	<10	13	20	10	694	2
121365	1.6	0.91	93	69	<0.5	<5	4.03	16	7	36	47	3.16	<1	0.15	<10	0.65	1953	2	0.01	1	895	924	1.55	<5	2	125	<5	<0.01	<10	<10	28	26	1836	3
121366	<0.2	0.86	42	66	<0.5	<5	2.58	3	7	45	16	2.83	<1	0.18	<10	0.56	1314	2	0.01	1	905	166	1.25	<5	1	135	<5	<0.01	<10	<10	26	<10	340	3
121367	<0.2	0.80	43	115	<0.5	<5	4.07	1	7	35	10	3.04	<1	0.18	<10	0.52	1714	2	0.01	1	979	39	1.20	<5	1	90	<5	<0.01	<10	<10	27	<10	116	3
121368	<0.2	0.53	55	95	<0.5	<5	2.45	1	8	43	12	2.99	<1	0.20	<10	0.45	1285	2	0.01	2	1081	23	1.34	<5	2	76	<5	<0.01	<10	<10	23	<10	112	3
121369	<0.2	0.59	58	80	<0.5	<5	2.88	2	8	30	14	2.71	<1	0.18	<10	0.47	1433	2	0.01	1	949	30	1.24	<5	2	89	<5	<0.01	<10	<10	21	<10	115	3
121370	<0.2	0.61	61	73	<0.5	<5	2.80	2	7	36	16	2.75	<1	0.20	<10	0.55	1575	2	0.01	1	965	17	1.14	<5	2	117	<5	<0.01	<10	<10	22	<10	118	3
121371	<0.2	0.53	99	63	<0.5	<5	3.84	2	8	33	21	3.14	<1	0.17	<10	0.52	1841	2	0.01	1	918	45	1.75	<5	2	175	<5	<0.01	<10	<10	16	<10	100	3
121372	<0.2	0.79	54	87	<0.5	<5	2.27	1	7	38	16	2.66	<1	0.17	<10	0.54	1489	2	0.01	1	834	31	1.24	<5	1	81	<5	<0.01	<10	<10	23	<10	37	3
121373	1.3	1.77	124	60	<0.5	<5	2.68	1	23	18	67	5.81	<1	0.23	<10	1.39	2882	<2	0.01	3	1335	133	3.23	9	4	86	<5	0.01	<10	12	93	<10	61	3
121374	1.4	1.55	185	60	<0.5	<5	3.50	3	21	15	15	5.53	<1	0.17	<10	1.27	3341	<2	0.01	2	1258	95	3.52	9	4	125	<5	0.01	<10	14	83	<10	125	2
121375	<0.2	0.84	5	230	0.8	<5	0.47	<1	7	81	<1	2.06	<1	0.44	<10	0.60	574	<2	0.04	5	687	11	0.02	5	2	40	5	0.11	<10	<10	38	<10	55	2
121376	0.5	2.24	116	54	<0.5	<5	6.03	1	20	12	10	5.96	<1	0.17	10	1.67	3774	<2	0.01	2	1386	49	1.90	8	6	174	<5	0.01	<10	18	99	<10	89	3
121377	0.5	2.74	55	77	<0.5	6	2.96	<1	24	12	34	6.89	<1	0.14	<10	2.02	2848	<2	0.02	2	1658	89	1.48	9	7	108	<5	0.01	<10	13	141	<10	106	3
121378	0.2	2.40	56	69	<0.5	<5	4.03	<1	20	9	15	6.11	<1	0.15	<10	1.64	2729	<2	0.02	2	1471	30	1.09	9	7	122	<5	0.01	<10	12	116	<10	86	3
121379	0.2	2.21	40	65	<0.5	<5	3.45	<1	22	6	37	6.02	<1	0.20	<10	1.35	2533	<2	0.01	2	1496	32	1.32	9	5	118	<5	0.01	<10	12	84	<10	95	3
121380	0.9	2.01	81	72	<0.5	<5	3.93	<1	25	9	85	6.00	<1	0.23	<10	1.40	2848	<2	0.01	3	1403	34	2.25	9	4	132	<5	0.01	<10	12	75	<10	74	3
121381	1.0	2.04	65	105	<0.5	<5	4.33	1	39	9	133	6.21	<1	0.34	<10	1.27	2907	<2	0.01	4	1649	61	1.76	10	5	179	<5	0.01	<10	13	71	<10	137	3
121382	0.6	1.52	52	142	<0.5	<5	5.92	1	25	17	54	5.04	<1	0.37	<10	1.10	3009	3	0.01	3	1581	48	1.37	8	5	314	<5	<0.01	<10	12	45	<10	109	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3395RJ**

Date : Oct-09-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth/Shipment 28

Sample type: Rock

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121383	0.6	2.30	54	88	<0.5	<5	4.69	<1	25	9	88	6.24	<1	0.32	10	1.36	2771	<2	0.01	3	1726	61	1.23	8	4	172	<5	0.02	<10	12	66	<10	126	3
121384	0.2	<0.01	28	86	0.5	<5	<0.01	<1	23	8	29	<0.01	<1	0.06	11	0.04	2244	<2	<0.01	2	1377	147	0.83	9	4	129	<5	0.08	<10	<10	58	<10	80	3
121385	<0.2	1.71	28	119	0.8	<5	4.24	<1	24	10	14	4.44	<1	0.35	11	0.78	2023	<2	0.01	3	1292	24	0.92	9	4	148	<5	0.11	<10	<10	55	<10	55	4
121386	0.2	1.64	44	129	<0.5	<5	4.20	2	26	12	30	4.52	<1	0.28	10	0.94	2346	<2	0.01	3	1292	158	1.02	8	4	103	<5	0.06	<10	<10	56	<10	267	2
121387	0.3	1.58	57	89	<0.5	<5	4.08	1	28	6	78	4.79	<1	0.26	<10	0.97	2448	<2	0.01	4	1437	60	1.13	8	4	129	<5	0.02	<10	10	54	<10	137	2
121388	<0.2	0.99	35	94	<0.5	<5	8.45	1	14	13	45	2.99	<1	0.24	<10	0.45	2661	<2	0.01	2	961	94	0.75	5	2	303	<5	0.01	<10	<10	25	<10	145	2
121389	<0.2	1.33	21	65	<0.5	<5	4.22	<1	16	7	48	3.54	<1	0.24	<10	0.90	2117	<2	0.01	2	1275	43	0.68	7	2	124	<5	<0.01	<10	<10	30	<10	65	2
121390	<0.2	<0.01	23	79	<0.5	<5	<0.01	<1	15	6	30	<0.01	<1	0.06	<10	0.04	2083	<2	<0.01	2	1173	45	0.69	6	2	125	<5	<0.01	<10	<10	36	<10	63	2
121391	<0.2	0.88	21	91	<0.5	<5	3.37	<1	16	3	22	4.30	<1	0.20	<10	0.99	1743	<2	0.01	2	1216	40	0.57	5	3	139	<5	<0.01	<10	<10	30	<10	70	2
121392	<0.2	0.19	44	63	<0.5	<5	3.42	2	6	21	17	2.20	<1	0.16	<10	0.44	1547	2	0.01	1	636	74	1.00	<5	2	143	<5	<0.01	<10	<10	7	<10	164	2
130063	19.3	1.75	80	170	<0.5	<5	4.13	11	15	6	30	4.53	<1	0.18	<10	1.24	1853	<2	0.01	1	1046	595	1.38	9	2	112	<5	0.01	<10	<10	49	17	1488	2
130064	4.0	2.41	48	86	<0.5	<5	3.31	1	20	6	46	5.59	<1	0.19	<10	1.55	1938	<2	0.02	1	1377	51	0.87	9	3	113	<5	0.01	<10	<10	73	<10	154	3
130065	2.0	2.60	56	113	<0.5	<5	3.50	1	22	5	42	6.37	<1	0.22	<10	1.66	2380	<2	0.01	2	1769	36	0.98	<5	4	121	<5	0.04	<10	16	108	<10	120	3
130066	3.6	1.73	185	71	<0.5	<5	10.24	6	17	54	32	5.05	<1	0.15	<10	1.15	4135	<2	0.01	2	1234	152	1.75	<5	3	222	<5	0.05	<10	23	67	<10	389	2
130067	2.3	1.39	348	106	<0.5	<5	4.44	13	23	8	135	5.16	<1	0.27	<10	0.67	1584	2	0.01	2	1482	46	2.64	<5	2	120	<5	<0.01	<10	<10	36	10	665	2
130068	3.4	0.69	391	89	<0.5	<5	8.68	39	10	46	55	3.65	<1	0.16	<10	0.40	2527	2	0.01	2	630	369	2.66	<5	1	218	<5	<0.01	<10	14	16	53	3519	1
130069	1.4	2.18	89	103	<0.5	<5	3.85	5	17	8	24	5.45	<1	0.24	<10	1.48	2122	<2	0.01	1	1550	140	1.07	<5	2	128	<5	<0.01	<10	13	58	<10	380	2
130070	0.7	1.36	251	104	<0.5	<5	4.11	5	15	7	26	4.84	<1	0.28	<10	0.95	1916	<2	0.01	1	1603	26	1.14	<5	2	120	<5	<0.01	<10	<10	38	<10	64	2
130071	2.3	0.68	185	118	<0.5	<5	3.47	11	10	31	39	3.49	<1	0.22	<10	0.39	1646	5	0.01	1	970	501	2.41	<5	1	118	<5	<0.01	<10	<10	19	17	1196	1
130072	1.7	0.30	208	92	<0.5	<5	2.96	5	11	32	97	2.93	<1	0.19	<10	0.16	1683	26	0.01	2	844	69	2.83	<5	1	112	<5	<0.01	<10	<10	8	<10	197	1
130073	3.3	0.37	249	80	<0.5	<5	2.74	5	13	55	165	4.01	<1	0.21	<10	0.17	1682	14	0.01	4	742	49	3.82	<5	1	95	<5	<0.01	<10	<10	10	<10	148	2
130074	3.8	0.49	255	77	<0.5	<5	5.72	6	11	45	170	3.11	<1	0.20	<10	0.28	2810	47	0.01	3	868	39	2.29	<5	1	164	<5	<0.01	<10	16	16	<10	179	1
130075	>200.0	0.58	561	162	<0.5	80	0.51	20	7	19	7541	2.21	6	0.14	<10	0.56	277	540	0.03	5	528	904	1.18	1668	1	73	<5	0.04	<10	<10	16	<10	902	2
130076	6.3	0.78	336	93	<0.5	<5	3.33	8	17	39	320	4.59	<1	0.24	<10	0.47	2692	50	0.01	4	1181	54	3.20	<5	1	129	<5	<0.01	<10	17	26	<10	304	1
130077	5.4	0.38	442	71	<0.5	<5	3.35	9	20	33	217	5.98	<1	0.25	<10	0.18	2008	146	0.01	4	1657	53	>5.00	<5	1	160	<5	<0.01	<10	11	12	<10	163	2
130078	10.8	0.41	442	70	<0.5	<5	3.74	9	18	36	258	5.64	<1	0.28	<10	0.33	2523	56	0.01	4	1545	128	4.97	<5	2	119	<5	<0.01	<10	18	19	<10	212	2
130079	6.6	0.61	275	77	<0.5	<5	4.03	8	14	30	326	4.61	<1	0.20	<10	0.40	3010	75	0.01	3	1444	309	3.43	<5	2	122	<5	<0.01	<10	18	32	<10	481	1
130080	5.7	0.80	203	88	<0.5	<5	2.75	5	15	25	385	4.60	<1	0.23	<10	0.45	2647	56	0.01	3	1699	36	3.17	<5	2	86	<5	<0.01	<10	16	39	<10	251	1
130081	3.0	0.38	260	72	<0.5	<5	3.33	6	16	30	157	3.82	<1	0.21	<10	0.18	1940	22	0.01	4	1218	44	3.59	<5	1	116	<5	<0.01	<10	<10	16	<10	150	1
130082	4.9	0.39	218	54	<0.5	<5	3.84	5	13	41	211	3.56	<1	0.18	<10	0.29	2455	136	0.01	1	1022	68	2.90	<5	2	142	<5	<0.01	<10	11	15	<10	210	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3395RJ**

Date : Oct-09-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth/Shipment 28

Sample type: Rock

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130083	4.0	0.91	537	71	<0.5	<5	2.38	12	19	28	219	5.38	<1	0.21	<10	0.54	1921	142	0.01	2	1601	67	3.67	<5	2	94	<5	<0.01	<10	10	37	<10	245	2
130084	2.9	1.89	340	82	<0.5	<5	2.78	7	24	16	173	6.60	<1	0.21	<10	1.32	2553	65	0.01	3	1942	42	2.30	<5	4	119	<5	<0.01	<10	13	84	<10	260	3
130085	2.4	1.42	199	116	<0.5	<5	6.39	4	21	22	143	5.33	<1	0.18	<10	1.25	3111	98	0.01	3	1621	28	1.45	<5	5	247	<5	<0.01	<10	19	68	<10	161	2
130086	2.3	1.55	247	62	<0.5	<5	7.59	7	19	15	117	5.29	<1	0.20	<10	0.99	3539	63	0.01	3	1683	33	2.31	<5	4	281	<5	<0.01	<10	21	71	<10	379	2
130087	1.9	1.67	250	162	<0.5	<5	7.86	5	18	17	133	5.04	<1	0.27	<10	0.98	3127	40	0.01	2	1484	25	1.88	<5	4	249	<5	<0.01	<10	19	68	<10	130	2
130088	0.9	1.22	756	129	<0.5	<5	9.11	16	15	14	43	4.36	<1	0.36	<10	0.63	3248	2	0.01	2	1486	94	1.83	<5	3	344	<5	<0.01	<10	18	52	<10	166	1
130089	0.6	1.32	133	124	<0.5	<5	11.58	3	15	11	28	3.93	<1	0.40	<10	0.64	4029	4	0.01	1	1404	69	1.29	<5	3	997	<5	<0.01	<10	22	36	<10	107	1
130090	1.9	1.08	346	108	<0.5	<5	5.37	7	18	22	57	4.39	<1	0.39	<10	0.41	2396	5	0.01	4	1418	175	2.95	<5	2	160	<5	<0.01	<10	10	32	<10	121	2
130091	1.2	1.84	229	146	<0.5	<5	2.93	5	19	6	71	4.99	<1	0.46	<10	0.84	1789	<2	0.01	3	1871	44	1.55	<5	3	84	<5	0.01	<10	<10	48	<10	124	2
130092	0.4	1.94	103	94	<0.5	<5	6.87	2	21	9	40	4.65	<1	0.39	11	1.02	2941	<2	0.02	3	1614	31	0.79	<5	3	190	<5	0.01	<10	16	54	<10	73	2
130093	0.8	1.85	118	114	<0.5	<5	5.32	2	18	6	63	4.70	<1	0.41	10	0.96	2530	<2	0.01	3	1738	40	1.01	<5	3	148	<5	0.01	<10	12	56	<10	91	2
130094	0.7	1.81	164	120	<0.5	<5	4.41	3	17	6	33	5.02	<1	0.30	<10	1.05	2542	<2	0.01	3	1533	70	1.43	<5	3	119	<5	<0.01	<10	13	68	<10	88	2
130095	0.7	2.12	78	126	<0.5	<5	5.08	3	17	9	41	5.40	<1	0.35	<10	1.34	2627	7	0.01	3	1569	123	1.20	<5	3	138	<5	<0.01	<10	15	72	<10	352	2
130096	5.9	0.68	82	66	<0.5	<5	>15.00	14	7	17	52	2.18	<1	0.24	<10	0.31	5587	<2	0.01	1	660	598	0.99	<5	2	360	<5	<0.01	<10	28	18	27	1809	<1
130097	1.4	0.77	234	117	<0.5	<5	7.24	6	12	25	16	3.82	<1	0.38	<10	0.22	2182	<2	0.01	3	984	165	2.97	<5	2	156	<5	<0.01	<10	<10	20	<10	348	1
130098	1.0	0.92	49	69	<0.5	<5	>15.00	14	9	15	20	3.53	<1	0.17	11	0.48	4753	<2	0.01	2	724	356	1.82	<5	2	299	<5	<0.01	<10	19	29	22	1529	<1
130099	6.0	2.08	38	137	<0.5	<5	4.52	50	18	16	76	5.93	<1	0.27	<10	1.38	2795	<2	0.01	3	1410	3485	2.07	<5	3	135	<5	0.01	<10	17	72	99	6463	2
130100	<0.2	1.09	<5	264	<0.5	<5	0.96	<1	9	108	<1	2.33	<1	0.54	<10	0.69	731	<2	0.08	6	914	20	0.01	<5	2	59	5	0.16	<10	<10	42	<10	94	2
130101	4.1	1.96	51	102	<0.5	<5	5.34	4	17	11	14	5.38	<1	0.24	<10	1.27	3122	<2	0.01	2	1380	2485	1.45	<5	2	149	<5	0.01	<10	17	63	<10	501	2
130102	0.3	2.14	56	119	<0.5	<5	4.96	1	19	8	35	5.60	<1	0.31	<10	1.36	2978	<2	0.01	3	1607	65	1.40	<5	3	138	<5	0.01	<10	16	65	<10	112	2
130103	0.5	1.39	253	141	<0.5	<5	5.24	6	18	8	20	5.49	<1	0.38	<10	0.85	2660	<2	0.01	3	1511	111	3.11	<5	2	147	<5	<0.01	<10	15	47	<10	243	2
130104	4.3	0.54	350	44	<0.5	<5	7.41	13	14	48	82	5.53	<1	0.32	<10	1.07	2655	<2	0.02	8	1184	750	4.05	<5	2	269	<5	<0.01	<10	19	21	12	757	2
130105	0.8	1.62	65	294	<0.5	<5	6.76	11	15	14	53	5.11	<1	0.29	<10	1.22	3559	<2	0.01	3	1383	490	1.26	<5	3	169	<5	<0.01	<10	18	51	17	1049	2
130106	0.2	0.97	104	224	<0.5	<5	7.00	3	10	11	24	3.95	<1	0.43	<10	0.39	2665	<2	0.01	1	1185	237	1.27	<5	1	141	<5	<0.01	<10	11	22	<10	194	1
130107	1.0	0.86	274	154	<0.5	<5	10.16	7	11	20	29	4.71	<1	0.29	<10	0.40	3496	<2	0.01	2	617	446	1.96	<5	1	265	<5	<0.01	<10	21	15	<10	242	2
130108	<0.2	0.55	14	418	<0.5	<5	3.53	<1	6	9	8	1.51	<1	0.44	13	0.21	1305	2	0.02	1	1230	12	0.14	<5	1	107	<5	<0.01	<10	<10	6	<10	41	1
130109	<0.2	0.77	18	168	<0.5	<5	2.93	1	9	6	9	2.45	<1	0.50	16	0.29	1421	3	0.02	1	1598	320	0.15	<5	1	63	<5	<0.01	<10	<10	12	<10	113	1
130110	<0.2	0.92	19	176	<0.5	<5	4.23	<1	10	7	17	3.85	<1	0.47	13	0.48	2191	3	0.02	1	1415	68	0.44	<5	1	87	<5	<0.01	<10	<10	18	<10	88	1
130111	<0.2	0.67	37	179	<0.5	<5	5.05	3	12	3	22	3.88	<1	0.49	12	0.49	2088	<2	0.02	1	1474	75	0.58	<5	2	99	<5	<0.01	<10	11	14	<10	380	2
WDR08-10	127.3	0.60	1187	125	<0.5	<5	1.31	66	7	53	255	4.18	<1	0.23	<10	0.26	971	<2	0.01	3	756	5514	1.91	33	1	32	<5	<0.01	<10	<10	21	78	5406	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3395RJ

Date : Oct-09-08

Ascot Resources Ltd.

Attention: Sue Deane

Project: Dilworth/Shipment 28

Sample type: Rock

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
WDR08-11	>200.0	0.50	1338	112	<0.5	5	0.19	55	4	43	591	8.82	1	0.20	<10	0.20	634	<2	0.01	1	674	9498	2.09	236	1	6	<5	<0.01	<10	17	16	65	4587	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3497-RA1

Company: **Ascot Resources Ltd**
 Project: **Dilworth/shipment 29**
 Attn: **Sue Dean**

Oct-09-08

We hereby certify the following assay of 22 core samples submitted Sep-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
121393	0.05	0.05	4.0	
121394	0.02		0.7	
121395	0.04		0.6	
121396	0.03		<0.1	
121397	0.05		0.5	
121398	0.08		0.2	
121399	0.05		<0.1	
121400	0.13		>200	793.2
121401	0.03		1.5	
121402	0.33	0.30	0.9	
121403	0.11		0.4	
121404	0.05		0.2	
121405	0.12		0.2	
121406	0.04		0.3	
121407	0.06		0.8	
121408	0.09		0.5	
121409	0.16		0.3	
121410	0.04		0.5	
121411	0.05		0.2	
121412	0.03	0.02	0.2	
121413	0.07		0.4	
121414	0.05		0.5	
*0211	2.06			
*CCu-1c				131.8
*BLANK	<0.01			<0.1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3497-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 29**
Attn: **Sue Dean**

Oct-09-08

We hereby certify the following assay of 22 pulp samples submitted Sep-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121415	0.05	0.04	0.2
121416	0.02		<0.1
121417	0.07		<0.1
121418	0.03		<0.1
121419	<0.01		<0.1
121420	0.03		<0.1
121421	0.14		<0.1
121422	0.11		0.2
121423	0.09		0.9
121424	0.03	0.04	0.7
121425	<0.01		<0.1
121426	0.05		2.7
121427	0.03		1.0
121428	0.04		0.5
121429	0.04		0.1
121430	0.04		<0.1
121431	0.02		<0.1
121432	0.03		0.7
121433	0.10		0.6
121434	0.14	0.15	1.0
121435	0.19		0.7
121436	0.08		0.5
*0211	2.21		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3497-RA3

Company: **Ascot Resources Ltd**
 Project: **Dilworth/shipment 29**
 Attn: **Sue Dean**

Oct-09-08

We hereby certify the following assay of 22 core samples submitted Sep-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
121437	0.07	0.07	0.6	
121438	0.04		0.4	
121439	0.09		0.7	
121440	0.07		0.7	
121441	0.06		0.7	
121442	0.04		0.3	
121443	0.06		0.8	
121444	0.08		0.9	
121445	0.14		1.7	
121446	0.09	0.09	4.1	
121447	0.04		1.1	
121448	2.35		1.4	
121449	0.04		0.9	
121450	0.11		>200	785.5
121451	0.04		2.9	
121452	0.02		1.9	
121453	0.04		1.8	
121454	0.08		1.2	
121455	0.02		1.3	
121456	0.04	0.03	0.9	
121457	0.04		0.9	
121458	0.02		0.8	
*0211	2.20			
*CCu-1c				131.3
*BLANK	<0.01			<0.1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3497-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 29**
Attn: **Sue Dean**

Oct-09-08

We hereby certify the following assay of 22 core samples submitted Sep-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121459	0.07	0.06	2.2
121460	0.05		2.7
121461	0.05		1.8
121462	0.07		2.2
121463	0.04		1.5
121464	0.03		1.9
121465	0.03		2.2
121466	0.07		2.0
121467	0.01		1.6
121468	0.02	0.01	1.4
121469	0.01		2.2
121470	0.01		1.9
121471	0.02		1.9
121472	0.03		2.2
121473	0.02		1.8
121474	0.04		1.7
121475	<0.01		<0.1
121476	0.01		1.3
121477	0.01		1.7
121478	0.06	0.06	2.6
121479	0.06		1.9
121480	0.11		6.3
*0211	2.21		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3497-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 29**
Attn: **Sue Dean**

Oct-09-08

We hereby certify the following assay of 22 core samples submitted Sep-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121481	0.66	0.69	7.4
121482	0.28		6.5
121483	0.58		10.1
121484	0.33		3.8
121485	0.28		6.0
121486	0.08		1.7
121487	0.07		3.0
121488	0.12		3.2
121489	0.39		12.5
121490	0.48	0.47	48.4
121491	0.32		7.3
121492	0.08		2.8
121493	0.04		2.1
121494	0.03		1.8
121495	0.06		1.8
121496	0.03		1.9
121497	0.01		1.2
121498	0.01		0.7
121499	0.06		1.9
121500	5.81	5.72	2.8
121501	0.11		7.9
121502	0.01		0.9
*0211	2.15		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3497-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 29**
Attn: **Sue Dean**

Oct-09-08

We hereby certify the following assay of 22 core samples submitted Sep-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121503	0.05	0.05	2.0
121504	0.04		7.7
121505	0.17		4.6
121506	0.07		2.1
121507	0.35		3.9
121508	0.34		5.5
121509	0.28		4.8
121510	0.25		3.9
121511	0.25		5.2
121512	0.06	0.05	2.6
121513	0.06		1.6
121514	0.11		1.6
121515	0.06		1.9
121516	0.03		1.7
121517	0.06		1.8
121518	0.03		1.9
121519	0.06		1.8
121520	0.10		2.2
121521	0.07		2.0
121522	0.09	0.09	2.5
121523	0.15		<0.1
121524	0.09		0.5
*0211	2.07		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3497-RA7

Company: **Ascot Resources Ltd**
 Project: **Dilworth/shipment 29**
 Attn: **Sue Dean**

Oct-09-08

We hereby certify the following assay of 22 core samples submitted Sep-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne	Zn %
121525	0.11	0.10	>200	795.9	
121526	<0.01		0.5		
121527	0.04		0.7		
121528	0.07		2.1		
121529	0.05		1.9		
121530	0.02		0.9		
121531	0.02		0.3		
121532	0.15		1.5		
121533	0.22		7.8		1.97
121534	0.23	0.23	4.0		1.13
130112	0.01		0.2		
130113	0.01		<0.1		
130114	0.12		0.4		
130115	0.11		0.6		
130116	0.16		0.8		
130117	0.10		0.8		
130118	0.08		0.9		
130119	0.10		1.3		
130120	0.04		1.1		
130121	0.04	0.03	0.5		
130122	0.08		0.8		
130123	0.03		0.6		
*0211	2.22				
*CCu-1c				131.8	3.92
*BLANK	<0.01			<0.1	<0.01

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3497-RA8

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 29**
Attn: **Sue Dean**

Oct-09-08

We hereby certify the following assay of 22 core samples submitted Sep-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130124	0.05	0.02	0.8
130125	0.48		<0.1
130126	0.02		0.8
130127	0.04		0.8
130128	0.07		1.0
130129	0.11		1.4
130130	0.05		2.2
130131	0.06		2.5
130132	0.14		1.7
130133	0.23	0.23	1.4
130134	0.22		5.6
130135	0.49		1.6
130136	0.05		0.6
130137	0.05		0.7
130138	0.08		1.5
130139	0.07		1.3
130140	0.05		1.5
130141	0.01		1.1
130142	0.01		0.4
130143	0.01	0.01	0.7
130144	0.01		0.5
130145	0.01		0.4
*0211	2.23		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3497-RA9

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 29**
Attn: **Sue Dean**

Oct-09-08

We hereby certify the following assay of 22 core samples submitted Sep-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130146	0.01	0.01	0.7
130147	<0.01		0.3
130148	0.03		0.4
130149	0.05		0.5
130150	0.01		<0.1
130151	0.04		0.5
130152	0.02		0.5
130153	0.07		1.5
130154	0.02		0.3
130155	0.03	0.03	2.9
130156	0.02		0.4
130157	0.02		0.9
130158	0.01		0.3
130159	0.02		2.6
130160	0.01		0.4
130161	0.01		0.8
130162	0.08		0.9
130163	0.01		0.4
130164	0.02		0.7
130165	0.16	0.15	4.3
130166	<0.01		0.6
130167	0.06		0.5
*0211	2.19		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3497-RA10

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 29**
Attn: **Sue Dean**

Oct-09-08

We hereby certify the following assay of 22 core samples submitted Sep-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130168	0.02	0.02	0.5
130169	<0.01		0.3
130170	<0.01		0.5
130171	0.17		1.6
130172	0.01		1.0
130173	0.02		0.8
130174	0.01		0.5
130175	6.38		3.2
130176	0.03		1.2
130177	0.02	<0.01	0.9
130178	0.01		0.4
130179	0.03		1.1
130180	0.08		3.1
130181	0.05		12.6
130182	0.05		49.9
130183	0.05		2.5
130184	0.36		5.2
130185	0.13		3.8
130186	0.20		4.0
130187	0.05	0.05	3.0
130188	0.04		3.4
130189	0.01		1.3
*0211	2.11		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3497-RA11

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 29**
Attn: **Sue Dean**

Oct-09-08

We hereby certify the following assay of 22 core samples submitted Sep-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130190	0.01	0.01	1.2
130191	0.08		4.0
130192	0.20		2.5
130193	0.01		1.0
130194	0.02		1.0
130195	0.01		1.2
130196	0.01		0.9
130197	0.02		0.3
130198	0.01		0.7
130199	0.01	0.01	<0.1
130200	0.01		<0.1
130201	0.01		<0.1
130202	0.01		<0.1
130203	0.08		0.2
130204	0.04		0.2
130205	0.02		0.3
130206	0.04		0.4
130207	0.05		0.4
130208	0.02		<0.1
130209	0.02	0.01	0.3
130210	0.01		0.2
130211	0.01		<0.1
*0211	2.23		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3497-RA12

Company: **Ascot Resources Ltd**
 Project: **Dilworth/shipment 29**
 Attn: **Sue Dean**

Oct-09-08

We hereby certify the following assay of 22 core samples submitted Sep-25-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
130212	0.02	0.02	0.3	
130213	0.01		<0.1	
130214	<0.01		<0.1	
130215	<0.01		<0.1	
130216	<0.01		<0.1	
130217	0.01		<0.1	
130218	0.01		<0.1	
130219	0.02		0.2	
130220	<0.01		<0.1	
130221	0.01	0.02	0.2	
130222	<0.01		0.3	
130223	0.02		0.2	
130224	<0.01		<0.1	
130225	0.11		>200	791.8
130226	<0.01		1.3	
130227	<0.01		0.5	
130228	0.01		0.5	
130229	0.01		0.4	
130230	0.02		0.5	
130231	0.01	0.02	0.2	
130232	<0.01		0.1	
130233	<0.01		<0.1	
*0211	2.18			
*CCu-1c				131.8
*BLANK	<0.01			<0.1

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3497RJ**

Date : Oct-09-08

Ascot Resources Ltd

Attention: Sue Dean

Project: Dilworth/shipment 29

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121393	4.0	0.27	56	123	<0.5	<5	4.61	1	7	40	16	2.87	<1	0.22	<10	0.58	1981	<2	0.01	2	922	53	1.11	<5	2	146	<5	<0.01	<10	<10	15	<10	153	2
121394	0.7	0.43	45	164	<0.5	<5	3.79	1	8	36	12	2.90	<1	0.20	<10	0.39	1433	2	0.01	2	1033	37	1.61	<5	2	95	<5	<0.01	<10	<10	21	<10	137	3
121395	0.6	0.28	56	129	<0.5	<5	6.21	1	7	35	12	2.51	<1	0.23	<10	0.31	1702	2	0.01	2	910	27	1.61	<5	2	143	<5	<0.01	<10	<10	10	<10	123	2
121396	<0.2	0.65	71	99	<0.5	<5	2.86	1	8	32	9	2.86	<1	0.23	<10	0.45	1256	3	0.02	2	1023	24	1.27	<5	2	86	<5	<0.01	<10	<10	29	<10	96	3
121397	0.5	0.50	56	86	<0.5	<5	3.18	1	8	42	10	3.03	<1	0.22	<10	0.43	1246	2	0.01	2	950	32	1.73	<5	2	81	<5	<0.01	<10	<10	23	<10	92	3
121398	0.2	0.33	44	106	<0.5	<5	3.67	1	7	40	9	3.13	<1	0.22	<10	0.51	1455	2	0.01	2	922	31	1.93	<5	2	126	<5	<0.01	<10	<10	14	<10	70	3
121399	<0.2	0.82	39	98	<0.5	<5	3.03	<1	8	46	9	3.17	<1	0.20	<10	0.69	1441	2	0.02	2	945	16	1.40	<5	2	87	<5	<0.01	<10	<10	31	<10	73	3
121400	>200.0	0.48	593	146	<0.5	104	0.51	19	6	18	7952	2.26	7	0.13	<10	0.51	273	589	0.03	5	754	976	1.27	1748	1	72	<5	0.03	<10	<10	12	<10	976	2
121401	1.5	0.90	41	80	<0.5	<5	3.06	<1	8	40	19	3.39	<1	0.20	<10	0.71	1534	3	0.02	2	1024	21	1.71	<5	2	94	<5	<0.01	<10	<10	28	<10	61	3
121402	0.9	0.67	51	89	<0.5	<5	4.48	1	7	43	10	2.91	<1	0.20	<10	0.52	1691	3	0.01	1	860	31	1.90	<5	1	121	<5	<0.01	<10	<10	20	<10	100	3
121403	0.4	0.50	63	77	<0.5	<5	3.98	1	6	42	7	2.75	<1	0.21	<10	0.43	1537	3	0.01	2	846	16	2.19	<5	1	124	<5	<0.01	<10	<10	14	<10	47	3
121404	0.2	0.44	71	83	<0.5	<5	3.12	1	7	45	5	2.89	<1	0.21	<10	0.39	1198	2	0.01	2	838	12	2.51	<5	1	99	<5	<0.01	<10	<10	13	<10	49	3
121405	0.2	0.46	96	98	<0.5	<5	3.72	1	8	30	4	3.22	<1	0.23	<10	0.55	1656	3	0.01	1	958	18	2.53	<5	1	131	<5	<0.01	<10	<10	13	<10	52	3
121406	0.3	1.09	82	91	<0.5	<5	3.84	1	13	27	6	4.11	<1	0.22	<10	0.95	2196	<2	0.01	2	1389	24	2.58	<5	2	122	<5	<0.01	<10	<10	38	<10	61	3
121407	0.8	1.79	134	72	<0.5	6	5.49	4	19	13	44	5.56	<1	0.23	<10	1.51	3438	<2	0.01	3	1733	86	2.46	<5	2	196	<5	<0.01	<10	22	54	<10	348	2
121408	0.5	1.15	172	84	<0.5	<5	4.23	5	18	14	31	4.83	<1	0.28	<10	0.93	2731	<2	0.01	3	1856	81	2.46	<5	2	166	<5	<0.01	<10	15	37	<10	348	2
121409	0.3	1.14	200	84	<0.5	<5	3.53	3	17	13	25	4.95	<1	0.28	<10	0.91	2493	<2	0.01	3	1669	18	2.03	<5	2	117	<5	<0.01	<10	11	37	<10	55	2
121410	0.5	1.56	61	72	<0.5	<5	3.66	1	17	13	46	4.82	<1	0.23	<10	1.45	2969	<2	0.01	2	1661	95	1.03	<5	3	134	<5	<0.01	<10	17	50	<10	177	2
121411	0.2	1.58	59	72	<0.5	<5	3.32	<1	19	8	36	5.17	<1	0.24	<10	1.29	2651	3	0.01	3	1832	22	1.27	<5	3	127	<5	<0.01	<10	16	46	<10	92	2
121412	0.2	1.76	39	62	<0.5	<5	3.69	<1	20	7	50	4.83	<1	0.23	<10	1.55	2632	<2	0.02	2	1825	19	0.89	<5	3	139	<5	<0.01	<10	15	47	<10	97	2
121413	0.4	1.01	133	76	<0.5	<5	4.60	3	16	13	28	5.02	<1	0.24	<10	0.98	2511	<2	0.01	2	1740	94	2.93	<5	2	204	<5	<0.01	<10	12	30	<10	198	2
121414	0.5	1.00	151	93	<0.5	5	4.53	3	18	19	28	4.97	<1	0.26	<10	1.20	2878	<2	0.01	3	1689	56	2.45	<5	2	191	<5	<0.01	<10	19	32	<10	161	2
121415	0.2	0.63	66	102	<0.5	<5	3.91	2	8	30	15	3.27	<1	0.26	<10	0.75	1877	2	0.01	1	882	114	1.48	<5	2	161	<5	<0.01	<10	<10	20	<10	186	3
121416	<0.2	0.87	55	88	<0.5	<5	3.94	2	7	34	11	3.18	<1	0.23	<10	0.70	1844	2	0.02	1	860	27	1.50	<5	2	114	<5	<0.01	<10	<10	29	<10	204	3
121417	<0.2	1.07	53	131	<0.5	<5	2.32	1	7	32	11	3.02	<1	0.24	11	0.72	1396	2	0.02	1	808	15	1.16	<5	2	64	<5	<0.01	<10	<10	33	<10	82	3
121418	<0.2	1.13	66	146	<0.5	<5	2.48	1	7	37	11	3.11	<1	0.26	11	0.73	1439	2	0.02	1	854	31	1.21	<5	2	64	<5	<0.01	<10	<10	35	<10	97	3
121419	<0.2	2.18	<5	1421	<0.5	<5	4.47	<1	18	46	22	4.93	<1	0.22	30	1.61	892	<2	0.03	12	2720	5	0.14	<5	4	112	<5	0.01	<10	<10	56	<10	139	4
121420	<0.2	1.03	53	175	<0.5	<5	3.91	1	7	36	11	2.97	<1	0.26	11	0.66	1578	2	0.02	1	806	50	1.33	<5	2	83	<5	<0.01	<10	<10	31	<10	111	3
121421	<0.2	0.88	123	119	<0.5	<5	4.97	2	8	21	4	3.64	<1	0.24	12	0.65	1784	5	0.01	1	869	18	2.65	<5	2	122	<5	<0.01	<10	<10	30	<10	38	3
121422	0.2	1.53	128	95	<0.5	<5	4.32	2	15	18	7	4.72	<1	0.29	10	1.12	2396	<2	0.01	2	1359	18	2.57	<5	3	118	<5	0.02	<10	13	54	<10	53	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3497RJ

Date : Oct-09-08

Ascot Resources Ltd

Attention: Sue Dean

Project: Dilworth/shipment 29

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121423	0.9	2.01	151	105	<0.5	<5	7.94	2	21	9	24	5.60	<1	0.30	11	1.42	3943	<2	0.01	2	1410	28	2.31	<5	4	264	<5	0.04	<10	25	67	<10	78	2
121424	0.7	2.16	68	93	<0.5	<5	4.25	<1	23	6	51	6.01	<1	0.30	<10	1.35	2656	<2	0.02	3	1616	17	1.60	<5	5	129	<5	0.03	<10	18	80	<10	99	3
121425	<0.2	0.98	<5	265	<0.5	<5	0.52	<1	8	98	<1	2.17	<1	0.47	<10	0.61	555	<2	0.07	6	728	2	0.01	<5	2	45	<5	0.14	<10	<10	39	<10	49	2
121426	2.7	2.40	95	84	<0.5	<5	6.06	1	25	6	25	6.50	<1	0.26	11	1.62	3543	<2	0.01	3	1666	1174	1.76	<5	5	166	<5	0.04	<10	24	90	<10	95	3
121427	1.0	2.28	72	98	<0.5	<5	4.10	6	26	8	70	6.42	<1	0.32	10	1.42	2657	<2	0.01	3	1735	232	1.94	<5	5	116	<5	0.06	<10	19	85	14	809	3
121428	0.5	2.16	69	115	<0.5	<5	4.85	1	21	9	35	5.66	<1	0.30	11	1.34	2764	<2	0.01	3	1571	38	1.39	<5	4	166	<5	0.03	<10	18	79	<10	114	3
121429	<0.2	0.91	67	123	<0.5	<5	5.74	4	5	40	9	2.49	<1	0.21	<10	0.55	1945	2	0.01	1	648	55	0.77	<5	2	119	<5	<0.01	<10	<10	30	<10	365	2
121430	<0.2	1.06	103	121	<0.5	<5	4.63	2	6	30	8	2.83	<1	0.28	10	0.64	1795	2	0.01	1	782	18	1.08	<5	2	99	<5	<0.01	<10	<10	29	<10	42	3
121431	<0.2	0.98	75	118	<0.5	<5	4.10	1	5	31	10	2.57	<1	0.26	<10	0.55	1699	2	0.01	1	677	51	0.72	<5	2	104	<5	<0.01	<10	<10	29	<10	43	3
121432	0.7	2.40	82	94	<0.5	<5	3.17	1	21	7	41	5.85	<1	0.27	<10	1.59	2657	<2	0.01	3	1521	21	0.89	<5	3	73	<5	0.09	<10	14	74	<10	88	3
121433	0.6	1.72	214	113	<0.5	<5	5.46	4	19	10	26	5.25	<1	0.29	<10	0.98	3107	<2	0.01	2	1470	52	2.12	<5	3	139	<5	0.08	<10	18	59	<10	229	2
121434	1.0	1.49	286	109	<0.5	<5	8.26	4	17	15	12	5.52	<1	0.25	<10	0.96	3922	<2	0.01	2	1383	84	3.11	<5	3	299	<5	0.04	<10	26	58	<10	86	2
121435	0.7	1.49	331	115	<0.5	5	5.54	5	15	15	10	5.20	<1	0.23	<10	1.02	3645	<2	0.01	3	1328	26	2.86	<5	3	166	<5	0.01	<10	22	57	<10	57	2
121436	0.5	0.48	153	63	<0.5	6	>15.00	3	5	23	5	2.07	<1	0.11	<10	0.36	4776	<2	0.01	<1	425	178	1.28	<5	2	303	<5	<0.01	<10	26	18	<10	54	<1
121437	0.6	1.59	152	124	<0.5	5	4.49	2	12	9	14	4.57	<1	0.24	<10	1.09	3931	<2	0.01	2	1381	35	1.74	<5	2	117	<5	<0.01	<10	20	45	<10	68	2
121438	0.4	0.78	101	158	<0.5	<5	5.80	1	9	16	12	3.70	<1	0.32	10	0.87	3834	<2	0.01	1	1271	29	1.68	<5	1	170	<5	<0.01	<10	21	18	<10	54	1
121439	0.7	1.96	144	102	<0.5	<5	3.75	2	18	9	25	5.56	<1	0.25	<10	1.22	3183	<2	0.01	2	1630	58	1.71	<5	4	86	<5	0.01	<10	16	77	<10	144	2
121440	0.7	1.48	119	88	<0.5	5	6.51	3	15	17	22	4.45	<1	0.24	10	0.90	3105	<2	0.01	2	1321	92	1.53	<5	3	124	<5	0.01	<10	14	57	<10	254	2
121441	0.7	2.31	96	105	<0.5	5	3.94	1	23	5	52	6.30	<1	0.27	12	1.57	3364	<2	0.01	2	1902	51	1.49	<5	5	104	<5	0.01	<10	18	98	<10	137	3
121442	0.3	1.74	118	92	<0.5	5	6.06	2	13	12	15	4.45	<1	0.29	<10	1.09	3167	<2	0.01	2	1410	17	1.19	<5	3	136	<5	0.01	<10	15	55	<10	89	2
121443	0.8	1.71	191	93	<0.5	5	7.67	4	15	8	43	4.83	<1	0.28	<10	1.02	3763	<2	0.01	1	1431	69	1.73	<5	3	161	<5	0.01	<10	18	51	<10	156	2
121444	0.9	0.56	128	73	<0.5	5	13.96	2	4	22	5	1.97	<1	0.14	<10	0.35	4439	2	0.01	<1	451	73	1.04	<5	2	249	<5	<0.01	<10	21	19	<10	21	1
121445	1.7	1.23	216	119	<0.5	5	5.45	4	12	13	18	4.04	<1	0.23	<10	0.78	4913	2	0.01	3	1093	408	2.13	<5	2	107	<5	<0.01	<10	25	43	<10	209	1
121446	4.1	0.92	165	73	<0.5	<5	13.14	10	8	16	437	3.30	<1	0.17	<10	0.57	5582	<2	0.01	2	771	808	1.91	<5	2	229	<5	<0.01	<10	25	31	18	1182	<1
121447	1.1	2.31	115	125	<0.5	5	5.51	3	18	5	51	5.73	<1	0.31	<10	1.37	4431	<2	0.01	3	1579	183	1.09	<5	3	127	<5	0.01	<10	24	72	<10	301	2
121448	1.4	2.07	91	108	<0.5	<5	5.61	3	18	4	66	5.11	<1	0.32	<10	1.13	3606	<2	0.01	3	1571	161	0.82	<5	3	140	<5	0.02	<10	18	66	<10	275	2
121449	0.9	2.14	101	138	<0.5	<5	3.53	3	19	3	50	5.47	<1	0.36	<10	1.12	3040	<2	0.01	3	1596	123	1.02	<5	3	92	<5	0.02	<10	17	64	<10	246	2
121450	>200.0	0.63	608	186	<0.5	105	0.56	20	7	21	7613	2.46	7	0.14	<10	0.59	299	573	0.03	5	655	949	1.28	1707	1	73	<5	0.05	<10	<10	18	<10	976	2
121451	2.9	2.11	88	151	<0.5	5	3.82	5	20	5	76	5.84	<1	0.27	<10	1.42	3820	<2	0.01	3	1517	195	0.90	<5	4	104	<5	<0.01	<10	21	78	10	623	2
121452	1.9	2.15	70	109	<0.5	<5	3.12	1	19	5	87	5.06	<1	0.30	<10	1.45	3189	<2	0.01	3	1564	34	0.71	<5	4	91	<5	0.01	<10	17	75	<10	151	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3497RJ

Date : Oct-09-08

Ascot Resources Ltd

Attention: Sue Dean

Project: Dilworth/shipment 29

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121453	1.8	2.23	115	113	<0.5	<5	3.33	1	20	4	80	5.78	<1	0.29	<10	1.41	3059	<2	0.01	3	1571	26	1.15	<5	4	98	<5	0.03	<10	17	84	<10	63	2
121454	1.2	1.88	87	105	<0.5	<5	2.87	1	20	4	47	4.81	<1	0.31	<10	1.15	2826	4	0.01	3	1541	22	1.08	<5	3	81	<5	0.03	<10	16	71	<10	82	2
121455	1.3	1.97	85	157	<0.5	<5	3.51	1	16	6	68	4.75	<1	0.28	<10	1.23	3537	<2	0.01	3	1504	23	0.65	<5	3	96	<5	0.02	<10	18	73	<10	104	2
121456	0.9	1.93	155	111	<0.5	<5	2.58	2	18	4	42	5.01	<1	0.31	<10	1.11	3028	<2	0.01	3	1516	25	0.91	<5	3	72	<5	0.01	<10	16	66	<10	87	2
121457	0.9	1.94	110	111	<0.5	<5	4.31	1	17	4	29	5.21	<1	0.30	<10	1.11	3181	<2	0.01	2	1462	18	1.18	<5	3	108	<5	0.04	<10	18	66	<10	69	2
121458	0.8	2.12	102	106	<0.5	<5	4.18	1	18	4	26	5.75	<1	0.30	<10	1.24	3597	<2	0.01	3	1457	16	1.23	<5	3	158	<5	0.03	<10	20	68	<10	81	2
121459	2.2	2.16	225	86	<0.5	5	1.98	6	29	129	98	6.27	<1	0.25	<10	1.45	2654	<2	<0.01	34	1748	176	2.09	<5	10	98	<5	<0.01	<10	16	121	<10	421	2
121460	2.7	2.52	382	52	<0.5	6	1.72	7	39	272	110	7.78	<1	0.13	<10	2.09	2538	<2	<0.01	55	2221	137	2.92	<5	14	57	<5	0.02	<10	16	181	<10	159	3
121461	1.8	2.56	237	101	<0.5	5	1.29	4	39	238	117	7.51	<1	0.18	<10	2.08	2545	<2	<0.01	46	2011	37	2.02	<5	14	40	<5	0.01	<10	13	184	<10	169	3
121462	2.2	2.45	344	67	<0.5	6	1.85	6	35	221	116	7.95	<1	0.18	<10	2.06	2342	<2	<0.01	44	2068	24	3.01	<5	13	67	<5	0.01	<10	14	152	<10	110	3
121463	1.5	2.65	219	92	<0.5	5	1.61	3	44	256	118	6.85	<1	0.27	<10	1.99	2183	<2	<0.01	45	2720	18	1.46	<5	14	46	<5	0.01	<10	10	173	<10	76	3
121464	1.9	3.09	250	78	<0.5	6	1.72	4	44	317	126	8.34	<1	0.16	<10	2.65	2284	<2	<0.01	48	2255	16	2.41	<5	17	51	<5	0.02	<10	15	237	<10	112	3
121465	2.2	3.04	454	83	<0.5	5	4.03	8	37	312	109	8.00	<1	0.12	<10	2.76	2796	<2	<0.01	40	2154	22	2.43	<5	19	96	<5	0.02	<10	16	213	<10	155	3
121466	2.0	2.01	493	82	<0.5	<5	3.93	9	33	208	107	6.74	<1	0.19	<10	1.73	2400	<2	<0.01	43	1914	17	3.60	<5	13	87	<5	0.03	<10	16	145	<10	120	3
121467	1.6	2.15	134	52	<0.5	<5	8.21	2	28	264	86	5.03	<1	0.07	<10	2.21	2580	<2	<0.01	35	1721	9	1.16	<5	15	393	<5	0.03	<10	12	196	<10	91	2
121468	1.4	2.34	168	45	<0.5	<5	6.64	2	35	298	77	5.27	<1	0.06	<10	2.37	3126	<2	<0.01	39	1794	14	0.87	<5	19	212	<5	0.06	<10	14	225	<10	76	2
121469	2.2	2.81	165	48	<0.5	<5	8.91	2	39	330	114	6.46	<1	0.05	<10	2.94	3725	<2	0.01	46	2024	10	1.24	<5	29	275	<5	0.10	<10	18	256	<10	67	3
121470	1.9	2.59	168	39	<0.5	<5	7.28	2	35	296	78	5.72	<1	0.04	<10	2.81	2832	<2	0.01	41	1817	9	1.20	<5	24	199	<5	0.08	<10	13	225	<10	69	3
121471	1.9	2.51	215	44	<0.5	<5	7.21	4	36	286	97	5.90	<1	0.07	<10	2.63	2939	<2	<0.01	42	1810	10	1.25	<5	22	218	<5	0.09	<10	14	212	<10	112	3
121472	2.2	2.06	277	67	<0.5	<5	7.21	5	39	281	95	5.71	<1	0.12	<10	2.01	2745	<2	<0.01	46	1976	12	1.84	<5	20	197	<5	0.10	<10	13	201	<10	77	3
121473	1.8	2.28	189	49	<0.5	<5	6.46	3	34	295	103	5.52	<1	0.08	<10	2.34	2808	<2	<0.01	41	1874	21	1.37	<5	19	148	<5	0.08	<10	11	219	<10	148	2
121474	1.7	2.40	318	48	<0.5	<5	9.55	6	37	302	88	6.22	<1	0.08	<10	2.36	3714	<2	<0.01	43	1910	43	1.78	<5	21	202	<5	0.07	<10	18	215	<10	130	3
121475	<0.2	0.99	5	242	<0.5	<5	0.77	<1	9	94	4	2.25	<1	0.41	<10	0.69	691	<2	0.06	7	813	2	0.03	<5	3	44	<5	0.13	<10	<10	47	<10	52	2
121476	1.3	2.28	147	57	<0.5	5	10.16	2	37	293	84	5.38	<1	0.08	<10	2.16	3911	<2	<0.01	42	1835	9	0.77	<5	22	252	<5	0.03	<10	17	208	<10	54	2
121477	1.7	2.27	193	64	<0.5	<5	8.10	3	37	302	95	5.52	<1	0.08	<10	2.21	3691	<2	<0.01	44	1891	13	0.98	<5	21	224	<5	0.06	<10	17	211	<10	79	2
121478	2.6	1.31	301	74	<0.5	5	12.53	5	27	149	65	5.21	<1	0.11	<10	1.18	4531	<2	<0.01	34	1310	24	3.21	<5	11	216	<5	0.03	<10	20	100	<10	51	1
121479	1.9	1.07	293	52	<0.5	<5	11.53	5	26	132	47	4.50	<1	0.16	<10	1.05	4094	2	<0.01	30	1371	21	3.51	<5	8	235	<5	0.04	<10	21	87	<10	58	1
121480	6.3	1.86	601	57	<0.5	7	7.03	11	35	177	89	9.01	<1	0.16	<10	1.99	6184	<2	<0.01	42	1541	55	>5.00	8	9	164	<5	0.04	<10	42	115	<10	174	3
121481	7.4	1.59	629	86	<0.5	5	4.60	13	40	119	80	6.66	<1	0.24	<10	1.45	4861	<2	<0.01	63	1890	216	>5.00	10	8	141	<5	0.01	<10	27	83	11	623	2
121482	6.5	1.49	913	102	<0.5	6	6.68	17	36	122	55	7.09	1	0.24	<10	1.42	5086	3	<0.01	50	2227	38	>5.00	16	8	196	<5	0.01	<10	29	83	<10	188	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3497RJ

Date : Oct-09-08

Ascot Resources Ltd

Attention: Sue Dean

Project: Dilworth/shipment 29

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121483	10.1	1.04	1018	57	<0.5	9	6.21	19	35	83	52	10.74	<1	0.29	<10	0.78	3166	<2	<0.01	46	2097	68	>5.00	28	6	170	<5	0.02	<10	28	50	<10	199	4
121484	3.8	1.17	636	64	<0.5	<5	4.59	11	31	87	57	6.76	<1	0.23	<10	1.00	2151	<2	<0.01	33	1647	22	>5.00	<5	6	125	<5	0.04	<10	13	49	<10	95	3
121485	6.0	0.85	761	49	<0.5	6	4.20	14	37	63	78	10.44	<1	0.30	<10	0.53	2091	<2	<0.01	46	1707	125	>5.00	<5	4	157	<5	0.02	<10	22	38	<10	283	4
121486	1.7	1.78	202	74	<0.5	<5	3.44	3	25	77	76	5.99	<1	0.18	<10	1.89	2852	3	<0.01	24	1703	22	3.47	<5	7	96	<5	0.03	<10	17	111	<10	98	2
121487	3.0	2.45	248	72	<0.5	<5	3.87	4	33	76	116	6.90	<1	0.17	<10	2.86	3445	<2	<0.01	21	1998	24	3.67	<5	9	112	<5	0.06	<10	21	142	<10	127	3
121488	3.2	2.46	261	70	<0.5	<5	2.13	4	31	68	97	7.64	<1	0.21	<10	2.81	3704	<2	<0.01	21	1955	19	4.67	<5	7	60	<5	0.04	<10	25	119	<10	78	3
121489	12.5	0.68	619	51	<0.5	<5	1.14	12	43	35	70	7.29	<1	0.28	<10	0.35	1866	<2	<0.01	46	1708	53	>5.00	<5	4	44	<5	0.02	<10	14	35	<10	141	3
121490	48.4	1.16	728	40	<0.5	6	0.89	16	51	51	108	9.53	<1	0.28	<10	0.66	4626	<2	0.01	64	1677	175	>5.00	11	6	45	<5	0.02	<10	31	50	15	911	3
121491	7.3	1.84	727	55	<0.5	6	0.84	14	35	63	91	7.73	2	0.26	<10	1.81	3929	<2	0.01	38	1686	35	>5.00	<5	6	46	<5	<0.01	<10	23	83	<10	234	2
121492	2.8	2.78	314	76	<0.5	<5	3.24	5	30	104	94	6.78	<1	0.12	<10	3.43	4216	<2	0.01	22	1903	26	2.94	<5	9	94	<5	0.03	<10	24	174	<10	127	2
121493	2.1	3.13	309	75	<0.5	<5	3.70	6	30	94	90	6.88	<1	0.12	<10	3.99	2820	<2	<0.01	21	1785	32	2.54	<5	10	108	<5	0.05	<10	17	172	<10	120	3
121494	1.8	2.88	196	92	<0.5	<5	3.94	3	29	100	78	6.15	<1	0.15	<10	3.61	2637	<2	0.01	20	1799	22	1.95	<5	9	119	<5	0.06	<10	14	171	<10	106	2
121495	1.8	2.88	576	74	<0.5	5	4.77	12	29	104	88	6.44	<1	0.14	<10	3.37	2945	<2	<0.01	21	1766	30	1.91	<5	9	141	<5	0.01	<10	14	162	<10	354	2
121496	1.9	2.57	147	77	<0.5	5	5.56	2	32	93	92	5.90	<1	0.13	<10	3.04	3238	<2	<0.01	21	1670	28	1.93	<5	9	157	<5	0.02	<10	15	166	<10	125	2
121497	1.2	2.23	165	99	<0.5	5	4.32	3	22	41	70	5.03	<1	0.14	<10	2.59	3072	<2	<0.01	13	1676	30	1.41	<5	6	130	<5	0.01	<10	15	116	<10	145	2
121498	0.7	2.30	96	94	<0.5	<5	5.71	1	17	40	69	4.64	<1	0.19	<10	2.33	3019	<2	<0.01	11	1755	13	0.60	<5	5	144	<5	0.02	<10	13	102	<10	57	2
121499	1.9	2.13	578	101	<0.5	5	5.28	12	16	32	129	4.75	<1	0.23	<10	1.98	3132	<2	<0.01	11	1867	97	1.00	<5	5	173	<5	0.01	<10	16	84	<10	248	2
121500	2.8	1.42	794	132	<0.5	183	8.83	15	52	73	489	6.52	13	0.16	13	0.39	930	150	0.04	81	1090	92	2.52	<5	3	114	<5	0.13	<10	<10	44	56	103	16
121501	7.9	1.98	320	107	<0.5	<5	4.62	7	16	32	540	4.69	<1	0.22	<10	1.86	3050	<2	<0.01	10	1812	85	1.18	<5	4	153	<5	0.01	<10	15	77	<10	300	2
121502	0.9	2.24	125	106	<0.5	<5	3.64	2	17	26	83	4.69	<1	0.23	<10	2.12	2526	<2	<0.01	11	1935	12	0.58	<5	4	137	<5	0.01	<10	14	69	<10	82	2
121503	2.0	2.32	542	92	<0.5	<5	5.26	11	19	32	95	4.82	<1	0.26	<10	2.17	2901	<2	0.01	13	1932	33	1.05	<5	4	201	<5	0.01	<10	16	70	<10	218	2
121504	7.7	2.15	450	116	<0.5	<5	2.95	10	26	36	407	5.57	<1	0.29	<10	1.75	2560	<2	0.01	17	2152	407	1.45	<5	5	108	<5	0.01	<10	14	70	<10	389	3
121505	4.6	1.40	1062	128	<0.5	<5	2.55	21	20	33	161	5.04	<1	0.31	<10	0.99	2053	<2	0.01	16	1943	89	2.75	<5	4	94	<5	0.01	<10	<10	42	<10	151	2
121506	2.1	2.67	1209	141	<0.5	5	3.94	23	18	33	91	6.22	<1	0.27	<10	2.47	3878	<2	0.01	12	2247	17	0.93	<5	5	150	<5	<0.01	<10	22	81	<10	191	2
121507	3.9	1.66	1213	122	<0.5	5	3.87	23	26	50	99	6.35	<1	0.29	<10	1.21	2575	<2	0.01	21	1836	30	3.41	<5	6	119	<5	<0.01	<10	15	69	<10	88	3
121508	5.5	2.23	1025	121	<0.5	6	1.27	19	41	54	118	8.06	<1	0.29	<10	1.78	2104	<2	0.01	28	1932	33	3.97	<5	7	56	<5	0.01	<10	13	94	<10	135	3
121509	4.8	1.61	1008	104	<0.5	6	2.64	19	38	57	88	7.44	<1	0.28	<10	1.34	2027	<2	0.01	27	2240	42	>5.00	<5	6	90	<5	0.01	<10	15	69	<10	62	3
121510	3.9	2.49	920	109	<0.5	6	4.23	17	38	79	114	7.15	<1	0.26	<10	2.40	3043	<2	0.01	21	2123	22	3.02	<5	7	116	<5	0.01	<10	17	114	<10	119	3
121511	5.2	2.30	608	120	<0.5	5	2.33	12	33	62	110	6.99	<1	0.25	<10	2.02	2226	<2	0.01	22	2051	17	2.64	<5	7	90	<5	0.01	<10	13	114	<10	128	3
121512	2.6	2.60	752	105	<0.5	6	3.80	14	30	55	119	7.55	<1	0.28	<10	2.10	2313	<2	0.02	16	2219	16	2.20	<5	8	139	<5	0.01	<10	14	109	<10	101	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3497RJ

Date : Oct-09-08

Ascot Resources Ltd

Attention: Sue Dean

Project: Dilworth/shipment 29

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121513	1.6	2.86	810	110	<0.5	5	3.55	15	33	66	101	6.95	<1	0.24	<10	2.75	2162	<2	0.01	19	2182	17	1.52	<5	7	122	<5	0.01	<10	12	126	<10	105	3
121514	1.6	2.94	387	112	<0.5	5	6.34	7	29	93	108	7.03	<1	0.21	<10	2.86	2650	<2	0.01	19	2103	10	1.52	<5	8	225	<5	0.02	<10	16	138	<10	98	3
121515	1.9	2.49	329	102	<0.5	<5	2.73	6	30	56	106	6.69	<1	0.24	<10	2.40	1744	<2	0.01	21	1949	15	2.16	<5	6	95	<5	0.03	<10	13	109	<10	98	3
121516	1.7	3.24	381	121	<0.5	5	3.80	7	31	71	123	7.67	<1	0.23	<10	3.24	2328	<2	0.01	20	2196	10	1.55	<5	9	142	<5	0.02	<10	13	160	<10	119	3
121517	1.8	2.82	674	113	<0.5	6	4.68	12	32	65	106	6.89	<1	0.22	<10	2.71	2093	<2	0.01	23	2025	11	1.68	<5	8	140	<5	0.01	<10	11	126	<10	111	3
121518	1.9	3.29	192	198	<0.5	5	3.64	3	33	76	114	7.56	<1	0.20	<10	3.36	2106	<2	0.01	23	2184	10	1.37	<5	9	129	<5	0.01	<10	12	152	<10	117	3
121519	1.8	2.59	398	189	<0.5	6	6.04	7	31	66	88	6.02	<1	0.21	<10	2.55	2548	<2	0.01	19	1746	10	1.36	<5	7	165	<5	<0.01	<10	14	113	<10	93	2
121520	2.2	2.90	1044	205	<0.5	5	3.35	20	34	72	129	6.73	<1	0.24	<10	3.09	2838	<2	0.01	22	2093	11	1.77	<5	8	101	<5	0.01	<10	16	134	<10	110	3
121521	2.0	3.30	465	118	<0.5	6	3.68	8	32	88	104	7.65	<1	0.20	<10	3.71	2971	<2	0.01	20	2157	16	2.35	<5	8	113	<5	0.01	<10	17	155	<10	98	3
121522	2.5	3.09	428	90	<0.5	5	3.23	8	31	97	106	7.22	<1	0.18	<10	3.63	2851	<2	0.01	21	1923	30	2.36	<5	8	91	<5	0.01	<10	15	148	<10	113	3
121523	<0.2	1.08	70	135	<0.5	<5	2.00	1	9	40	11	3.58	<1	0.27	13	0.71	1458	2	0.01	2	1086	22	1.33	<5	2	50	<5	<0.01	<10	<10	34	<10	98	3
121524	0.5	2.01	68	155	<0.5	5	2.17	1	21	14	40	6.63	<1	0.24	<10	1.60	2147	<2	0.02	3	1770	41	2.15	<5	5	67	<5	0.01	<10	11	92	<10	118	3
121525	>200.0	0.59	601	181	<0.5	103	0.57	20	7	21	7612	2.46	6	0.13	<10	0.63	289	567	0.03	5	573	933	1.24	1699	1	72	<5	0.05	<10	<10	18	<10	954	2
121526	0.5	1.98	9	1291	<0.5	5	3.55	<1	20	51	38	5.92	<1	0.15	25	1.78	1204	<2	0.03	13	2963	13	0.29	<5	4	120	<5	0.01	<10	<10	78	<10	222	5
121527	0.7	2.09	83	115	<0.5	6	3.85	4	22	12	45	6.79	<1	0.20	<10	1.62	2935	<2	0.01	3	1739	280	2.00	<5	4	96	<5	0.01	<10	17	89	<10	401	2
121528	2.1	1.89	120	136	<0.5	5	6.03	10	19	10	76	6.35	<1	0.14	<10	1.55	3551	<2	0.01	2	1623	1035	2.35	<5	4	147	<5	0.01	<10	18	97	17	1065	2
121529	1.9	1.86	66	97	<0.5	5	4.79	17	21	7	108	6.29	<1	0.18	<10	1.46	3237	6	0.01	2	1702	1215	2.05	<5	4	160	<5	0.01	<10	20	73	30	1903	2
121530	0.9	2.15	22	111	<0.5	<5	3.58	<1	22	5	92	6.88	<1	0.18	10	1.52	2368	19	0.02	2	1837	39	0.62	<5	7	119	<5	0.02	<10	13	100	<10	145	3
121531	0.3	2.31	40	82	<0.5	<5	3.36	1	24	6	38	6.67	<1	0.18	<10	1.87	2839	<2	0.01	2	1843	80	1.17	<5	5	155	<5	0.07	<10	18	97	<10	161	3
121532	1.5	1.61	337	88	<0.5	7	7.63	22	19	15	23	7.47	<1	0.17	<10	1.27	4468	2	0.01	2	1418	492	4.86	<5	3	188	<5	0.01	<10	29	63	33	2030	3
121533	7.8	1.07	383	63	<0.5	9	7.04	198	18	21	343	8.37	<1	0.12	<10	0.84	3622	<2	0.01	2	1068	4884	>5.00	<5	2	145	<5	0.01	<10	23	53	369	>10000	3
121534	4.0	1.07	402	83	<0.5	7	5.30	109	20	22	107	7.91	<1	0.10	<10	0.88	3209	<2	0.01	3	1003	1587	>5.00	<5	2	102	<5	0.01	<10	22	66	201	>10000	3
130112	0.2	0.87	41	578	<0.5	<5	5.24	2	12	8	32	3.79	<1	0.24	<10	0.49	1808	<2	0.02	2	1097	47	0.54	<5	1	134	<5	<0.01	<10	<10	13	<10	206	1
130113	<0.2	0.89	17	223	<0.5	<5	5.18	1	9	5	32	2.50	<1	0.31	13	0.34	1749	<2	0.02	1	1626	17	0.25	<5	1	107	<5	<0.01	<10	<10	12	<10	102	1
130114	0.4	0.98	174	109	<0.5	<5	5.37	5	12	9	28	3.74	<1	0.24	<10	0.44	2094	<2	0.01	2	1100	42	1.11	<5	1	118	<5	<0.01	<10	<10	16	<10	240	1
130115	0.6	1.57	265	156	<0.5	5	2.62	6	14	25	44	6.29	<1	0.24	<10	0.73	1664	2	0.01	6	1860	39	2.10	<5	4	45	<5	<0.01	<10	<10	42	<10	231	2
130116	0.8	1.22	319	164	<0.5	<5	2.89	6	10	29	68	5.15	<1	0.35	<10	0.46	1445	<2	0.01	5	1380	19	2.17	<5	3	45	<5	<0.01	<10	<10	26	<10	49	2
130117	0.8	2.13	170	129	<0.5	6	4.88	4	25	40	52	6.60	<1	0.32	<10	1.07	2429	<2	0.02	9	1892	25	1.28	<5	5	85	<5	0.01	<10	14	64	<10	214	2
130118	0.9	1.93	209	138	<0.5	6	5.49	4	23	14	65	6.18	<1	0.33	10	0.95	2327	<2	0.02	8	1400	14	1.43	<5	3	97	<5	0.01	<10	13	49	<10	86	2
130119	1.3	2.39	109	134	<0.5	7	9.07	1	29	7	104	6.46	<1	0.34	<10	1.36	3259	<2	0.02	7	1599	13	0.68	<5	3	169	<5	<0.01	<10	16	61	<10	99	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3497RJ

Date : Oct-09-08

Ascot Resources Ltd

Attention: Sue Dean

Project: Dilworth/shipment 29

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130120	1.1	1.85	57	155	<0.5	<5	4.09	1	20	11	109	4.85	<1	0.33	<10	0.93	1794	10	0.02	6	1455	8	0.57	<5	3	71	<5	<0.01	<10	<10	55	<10	77	2
130121	0.5	2.35	23	129	<0.5	6	3.93	<1	21	45	54	6.65	<1	0.28	<10	1.24	2069	<2	0.02	10	1969	7	0.62	<5	5	74	<5	0.01	<10	11	66	<10	92	3
130122	0.8	2.13	91	122	<0.5	5	3.21	1	19	44	45	6.18	<1	0.27	<10	1.34	1818	<2	0.01	8	1865	36	1.19	<5	5	63	<5	0.01	<10	<10	63	<10	105	2
130123	0.6	2.39	35	128	<0.5	5	3.26	<1	23	49	50	6.12	<1	0.28	<10	1.64	1881	<2	0.02	10	2027	17	0.52	<5	5	64	<5	0.01	<10	<10	64	<10	121	2
130124	0.8	2.52	43	133	<0.5	5	3.65	<1	22	43	61	6.40	<1	0.28	<10	1.71	2001	<2	0.01	10	2109	16	0.75	<5	5	70	<5	0.01	<10	10	67	<10	138	2
130125	<0.2	0.97	7500	26	<0.5	20	6.78	150	191	14	73	4.23	<1	0.04	11	0.26	767	17	0.07	35	1554	13	1.53	<5	1	90	<5	0.05	<10	<10	39	<10	106	10
130126	0.8	2.22	91	119	<0.5	5	5.12	2	23	29	47	5.50	<1	0.27	<10	1.69	2255	2	0.01	8	1908	24	0.66	<5	5	122	<5	<0.01	<10	11	61	<10	131	2
130127	0.8	2.41	95	97	<0.5	5	4.28	2	19	26	45	5.96	<1	0.22	<10	2.01	1996	<2	0.01	7	1932	13	0.85	<5	4	85	<5	<0.01	<10	12	66	<10	125	2
130128	1.0	1.82	283	120	<0.5	5	4.45	5	20	21	42	5.58	<1	0.27	<10	1.42	1782	<2	0.01	7	1905	35	2.01	<5	4	94	<5	<0.01	<10	11	47	<10	121	2
130129	1.4	1.87	2666	111	<0.5	6	7.61	57	25	71	57	5.85	<1	0.25	<10	1.48	2839	<2	0.01	18	1683	471	1.72	<5	7	190	<5	<0.01	<10	17	76	11	687	2
130130	2.2	2.14	358	116	<0.5	6	6.48	22	25	30	123	6.14	<1	0.26	<10	1.71	2534	<2	0.01	11	1908	892	2.04	<5	6	139	<5	<0.01	<10	15	95	27	1767	2
130131	2.5	2.20	532	94	<0.5	7	6.67	36	26	42	109	6.74	<1	0.22	<10	1.99	2591	<2	0.01	12	1823	952	2.67	<5	7	144	<5	<0.01	<10	15	99	47	3155	2
130132	1.7	2.13	2915	89	<0.5	7	8.65	73	19	39	73	5.82	<1	0.19	<10	1.78	3097	<2	0.01	9	1511	1006	1.68	<5	7	162	<5	<0.01	<10	15	99	32	2085	2
130133	1.4	1.93	2563	93	<0.5	6	6.96	70	22	46	89	5.80	<1	0.20	<10	1.57	2709	<2	0.01	11	1592	985	2.09	<5	6	143	<5	<0.01	<10	14	96	29	1881	2
130134	5.6	1.54	1209	91	<0.5	7	9.62	71	18	36	193	5.00	<1	0.18	<10	1.23	2884	<2	0.01	8	1440	3821	2.36	<5	5	223	<5	<0.01	<10	16	72	80	5174	2
130135	1.6	2.17	1395	119	<0.5	6	8.29	30	28	33	120	5.99	<1	0.26	<10	1.78	2387	<2	0.01	11	1970	414	2.02	<5	6	170	<5	0.01	<10	13	99	<10	353	2
130136	0.6	1.72	194	118	<0.5	5	6.77	10	24	43	75	4.60	<1	0.24	<10	1.31	2265	4	0.01	11	1813	128	1.28	<5	5	140	<5	0.01	<10	10	75	12	772	2
130137	0.7	1.95	142	113	<0.5	6	6.32	9	20	28	82	4.81	<1	0.23	<10	1.52	2137	<2	0.01	9	1804	31	1.13	<5	5	126	<5	0.01	<10	10	81	12	725	2
130138	1.5	1.90	172	105	<0.5	7	7.72	26	23	31	119	5.38	<1	0.23	<10	1.38	2597	<2	0.01	10	1650	538	1.65	<5	6	164	<5	0.01	<10	16	86	37	2390	2
130139	1.3	2.33	684	109	<0.5	7	6.93	17	32	50	95	6.68	<1	0.21	<10	2.12	2267	<2	0.01	16	1779	88	2.44	<5	8	143	<5	0.01	<10	13	127	<10	449	2
130140	1.5	1.34	452	86	<0.5	7	12.32	73	17	42	137	4.10	<1	0.17	<10	1.04	2873	<2	0.01	9	1113	147	1.83	<5	7	231	<5	<0.01	<10	14	78	91	5865	1
130141	1.1	2.47	239	109	<0.5	6	7.18	17	31	63	118	6.67	<1	0.18	<10	2.42	1927	<2	0.01	17	1723	56	2.48	<5	10	143	<5	0.01	<10	10	159	16	944	3
130142	0.4	2.42	111	86	<0.5	6	5.75	3	27	57	66	5.85	<1	0.12	<10	2.75	1621	<2	0.02	15	1715	24	1.82	<5	11	127	<5	0.01	<10	<10	168	<10	184	2
130143	0.7	3.10	83	74	<0.5	7	5.18	3	31	76	91	7.29	<1	0.09	<10	3.68	1872	<2	0.02	18	1726	63	2.03	<5	14	118	<5	0.01	<10	10	210	<10	256	3
130144	0.5	2.34	82	78	<0.5	6	5.83	3	28	67	76	6.53	1	0.09	<10	2.86	1823	<2	0.02	16	1692	85	2.68	<5	13	146	<5	0.01	<10	<10	195	<10	285	3
130145	0.4	2.66	124	77	<0.5	5	5.19	3	31	64	80	6.76	<1	0.11	<10	3.30	1803	<2	0.02	17	1665	29	2.29	<5	13	137	<5	0.02	<10	10	191	<10	201	3
130146	0.7	2.34	202	72	<0.5	<5	4.09	8	26	57	68	5.27	<1	0.09	<10	2.92	1608	<2	0.01	13	1508	123	1.64	<5	10	99	<5	0.04	<10	<10	161	<10	503	2
130147	0.3	2.55	127	63	<0.5	<5	3.76	3	28	58	61	6.01	<1	0.06	<10	3.19	1647	<2	0.01	13	1605	18	1.91	<5	13	87	<5	0.05	<10	10	195	<10	179	3
130148	0.4	2.21	879	100	<0.5	5	4.18	18	29	57	67	5.79	<1	0.06	<10	2.59	1639	<2	0.01	15	1485	31	1.98	<5	12	92	<5	0.01	<10	<10	191	<10	179	3
130149	0.5	2.02	1782	81	<0.5	6	5.86	36	25	55	63	5.53	<1	0.09	<10	2.19	1936	<2	0.01	14	1460	32	2.06	<5	9	121	<5	0.01	<10	<10	155	<10	121	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3497RJ

Date : Oct-09-08

Ascot Resources Ltd

Attention: Sue Dean

Project: Dilworth/shipment 29

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130150	<0.2	0.92	16	248	<0.5	<5	0.59	<1	8	101	2	2.19	<1	0.35	<10	0.65	590	<2	0.06	6	810	3	0.04	<5	2	41	<5	0.13	<10	<10	42	<10	56	2
130151	0.5	2.22	945	57	<0.5	6	6.25	23	23	61	68	5.82	<1	0.07	<10	2.37	2277	<2	0.01	13	1399	129	1.77	<5	11	128	<5	0.01	<10	11	171	10	581	2
130152	0.5	2.36	129	68	<0.5	6	5.50	3	29	57	73	6.22	<1	0.07	<10	2.62	2116	<2	0.01	13	1546	66	2.03	<5	12	132	<5	0.01	<10	12	200	<10	162	3
130153	1.5	1.81	1144	54	<0.5	7	7.19	71	20	55	128	5.65	<1	0.09	<10	1.71	2280	<2	0.01	12	1280	1245	2.33	<5	8	166	<5	0.01	<10	14	124	72	4667	2
130154	0.3	2.42	310	104	<0.5	6	4.92	7	28	59	81	6.27	<1	0.09	<10	2.63	1885	<2	0.01	14	1480	110	1.84	<5	11	106	<5	0.01	<10	10	178	<10	207	3
130155	2.9	2.65	351	52	<0.5	6	5.85	45	24	70	206	6.61	<1	0.05	<10	2.71	2435	<2	0.01	13	1394	2178	1.74	<5	14	145	<5	0.01	<10	12	195	59	3800	3
130156	0.4	2.52	127	62	<0.5	5	6.27	7	24	71	78	5.80	<1	0.06	<10	2.57	2156	<2	0.01	13	1533	199	0.95	<5	15	135	<5	0.02	<10	10	209	10	592	2
130157	0.9	2.16	145	56	<0.5	6	6.88	69	23	60	211	5.70	1	0.05	<10	2.13	2267	<2	0.01	12	1275	343	1.69	<5	13	148	<5	0.02	<10	12	174	101	6458	2
130158	0.3	2.34	87	55	<0.5	5	5.76	14	27	74	90	5.78	1	0.05	<10	2.59	2036	<2	0.01	15	1536	32	1.27	<5	15	141	<5	0.01	<10	11	208	21	1319	2
130159	2.6	2.48	399	61	<0.5	6	6.69	46	25	65	229	6.02	<1	0.07	<10	2.50	2380	<2	0.01	14	1448	970	1.28	<5	13	140	<5	0.02	<10	11	178	56	3692	2
130160	0.4	2.14	106	65	<0.5	<5	6.45	5	22	60	68	5.05	<1	0.07	<10	2.22	2011	<2	0.01	12	1390	19	0.90	<5	11	138	<5	0.05	<10	10	162	<10	354	2
130161	0.8	2.44	400	64	<0.5	<5	5.42	11	27	68	84	5.69	<1	0.06	<10	2.64	1917	<2	0.01	14	1463	122	1.01	<5	14	124	<5	0.05	<10	10	193	<10	397	3
130162	0.9	2.47	1585	55	<0.5	<5	4.86	31	26	68	68	5.83	<1	0.05	<10	2.82	1829	<2	0.01	14	1439	20	1.44	<5	13	124	<5	0.07	<10	10	191	<10	109	3
130163	0.4	2.23	160	56	<0.5	<5	4.75	3	28	60	76	5.63	1	0.04	<10	2.55	1568	<2	0.01	13	1541	6	1.62	<5	15	120	<5	0.07	<10	<10	216	<10	81	3
130164	0.7	2.54	141	64	<0.5	<5	3.97	2	29	67	82	6.35	<1	0.05	<10	2.73	1708	<2	0.02	15	1606	14	1.64	<5	15	99	<5	0.10	<10	<10	204	<10	112	4
130165	4.3	1.88	4674	61	<0.5	<5	4.53	96	27	52	76	6.21	<1	0.05	<10	1.96	1787	<2	0.01	14	1556	351	2.69	21	12	120	<5	0.05	<10	12	177	12	734	3
130166	0.6	2.02	341	57	<0.5	<5	4.12	6	26	56	67	5.58	<1	0.05	<10	2.14	1658	<2	0.02	12	1513	9	1.85	<5	11	109	<5	0.10	<10	<10	165	<10	96	3
130167	0.5	2.10	361	68	<0.5	<5	4.49	7	28	61	75	5.64	<1	0.08	<10	2.24	1665	<2	0.01	13	1497	16	1.83	<5	12	119	<5	0.09	<10	<10	173	<10	85	3
130168	0.5	2.88	2542	68	<0.5	<5	6.22	53	33	79	86	7.20	<1	0.09	<10	2.99	2077	<2	0.02	18	1683	14	2.33	13	17	167	<5	0.10	<10	11	231	<10	108	4
130169	0.3	2.42	1075	69	<0.5	<5	5.56	21	31	80	78	6.64	<1	0.09	<10	2.48	1745	<2	0.02	16	1710	9	2.26	<5	14	147	<5	0.09	<10	<10	212	<10	83	3
130170	0.5	2.44	255	71	<0.5	<5	6.84	4	33	77	85	6.80	1	0.09	<10	2.50	1945	<2	0.02	17	1746	28	2.58	<5	15	170	<5	0.08	<10	<10	217	<10	87	3
130171	1.6	2.35	1305	70	<0.5	<5	7.43	26	33	75	83	6.70	<1	0.09	<10	2.36	2115	<2	0.02	17	1827	125	2.75	<5	14	195	<5	0.08	<10	12	204	<10	108	3
130172	1.0	2.58	204	73	<0.5	5	6.18	4	32	57	97	6.77	1	0.10	<10	2.79	2091	<2	0.02	17	1903	14	1.90	<5	12	183	<5	0.03	<10	13	200	<10	114	3
130173	0.8	2.96	222	90	<0.5	5	6.01	4	31	64	100	7.29	<1	0.12	<10	3.23	2168	<2	0.02	16	1827	29	2.36	<5	11	140	<5	0.05	<10	13	199	<10	124	3
130174	0.5	2.90	203	74	<0.5	<5	6.54	3	31	74	85	6.74	<1	0.09	<10	3.33	2199	<2	0.03	17	1798	15	2.00	<5	13	166	<5	0.05	<10	13	208	<10	115	3
130175	3.2	1.70	891	154	<0.5	201	10.70	18	59	86	542	7.27	15	0.15	15	0.42	1100	164	0.05	90	1219	104	2.83	<5	4	129	<5	0.16	<10	<10	52	64	116	20
130176	1.2	3.66	566	68	<0.5	5	5.16	12	33	78	93	7.82	<1	0.08	<10	4.23	2327	<2	0.03	17	1804	201	2.04	<5	14	111	<5	0.06	<10	15	232	<10	298	3
130177	0.9	2.37	163	70	<0.5	<5	7.15	5	31	61	129	5.96	<1	0.11	<10	2.48	2022	<2	0.02	15	1727	145	2.09	<5	10	136	<5	0.10	<10	<10	166	<10	286	3
130178	0.4	2.72	97	72	<0.5	<5	5.28	1	35	64	97	7.25	<1	0.11	<10	2.96	1647	<2	0.02	17	1816	12	2.97	<5	11	98	<5	0.11	<10	<10	195	<10	103	3
130179	1.1	2.79	348	62	<0.5	<5	7.18	6	34	68	85	7.15	<1	0.09	<10	3.02	2025	<2	0.02	16	1734	14	2.85	<5	13	148	<5	0.07	<10	13	198	<10	90	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3497RJ

Date : Oct-09-08

Ascot Resources Ltd

Attention: Sue Dean

Project: Dilworth/shipment 29

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130180	3.1	2.38	1643	77	<0.5	<5	8.28	34	28	60	77	6.17	<1	0.12	<10	2.52	2326	<2	0.06	14	1613	113	2.32	<5	10	168	<5	0.06	<10	13	160	<10	322	7
130181	12.6	2.66	316	70	<0.5	5	6.28	6	32	71	88	7.18	<1	0.10	<10	2.95	1997	<2	0.02	17	1699	52	3.03	<5	13	122	<5	0.05	<10	12	202	<10	138	3
130182	49.9	2.62	567	80	<0.5	6	6.22	11	30	68	102	6.72	<1	0.13	<10	2.76	2077	<2	0.02	17	1857	192	2.68	19	11	146	<5	0.01	<10	11	180	<10	217	3
130183	2.5	2.30	388	87	<0.5	<5	6.01	7	30	55	92	6.01	<1	0.16	<10	2.34	1917	<2	0.02	17	1850	19	2.46	<5	8	124	<5	0.05	<10	11	133	<10	103	2
130184	5.2	1.25	6618	48	<0.5	8	>15.00	144	20	36	79	5.20	<1	0.10	<10	1.11	3482	<2	0.01	11	975	334	3.15	42	5	339	<5	0.02	<10	19	65	20	1294	2
130185	3.8	1.62	2096	62	<0.5	5	12.45	44	24	41	96	5.20	<1	0.14	<10	1.41	3119	<2	0.02	12	1300	135	2.43	<5	7	265	<5	0.04	<10	18	91	<10	246	2
130186	4.0	1.58	5190	69	<0.5	6	10.67	106	22	52	67	5.23	<1	0.12	<10	1.41	2989	<2	0.02	12	1398	116	2.34	24	7	215	<5	0.03	<10	16	104	<10	252	2
130187	3.0	2.77	508	82	<0.5	5	7.56	10	33	69	81	7.23	<1	0.15	<10	2.69	2471	<2	0.02	17	1729	37	2.56	<5	10	144	<5	0.06	<10	15	166	<10	137	3
130188	3.4	2.87	394	89	<0.5	6	6.58	7	35	60	113	6.92	<1	0.16	<10	2.76	2532	<2	0.02	17	1841	94	1.85	<5	10	134	<5	0.03	<10	15	166	<10	124	3
130189	1.3	2.65	186	85	<0.5	<5	7.51	3	31	61	85	6.40	<1	0.16	<10	2.43	2226	<2	0.02	17	1748	10	1.60	<5	10	151	<5	0.07	<10	11	160	<10	97	3
130190	1.2	2.41	169	65	<0.5	7	8.20	3	28	56	76	6.25	<1	0.12	<10	2.19	2222	<2	0.01	14	1517	17	1.65	<5	8	181	<5	0.01	<10	15	130	<10	80	2
130191	4.0	2.11	2249	63	<0.5	9	10.40	46	29	44	103	6.80	<1	0.13	<10	1.64	2790	<2	0.01	15	1678	452	2.84	<5	6	208	<5	0.01	<10	18	96	<10	170	2
130192	2.5	1.33	7609	56	<0.5	8	12.03	173	23	42	66	5.13	<1	0.11	<10	1.10	3252	<2	0.01	12	1254	426	2.53	20	5	273	<5	<0.01	<10	19	64	30	1949	1
130193	1.0	2.71	229	57	<0.5	5	7.42	4	29	60	71	6.58	<1	0.09	<10	2.61	2208	<2	0.01	15	1559	14	1.45	<5	9	162	<5	0.05	<10	14	149	<10	111	3
130194	1.0	2.45	134	53	<0.5	6	7.65	2	32	83	97	6.32	<1	0.08	<10	2.33	2114	<2	0.01	18	1607	9	1.70	<5	11	168	<5	0.02	<10	12	173	<10	93	2
130195	1.2	1.93	276	69	<0.5	5	7.86	5	31	36	263	5.42	1	0.10	<10	1.74	2063	<2	0.01	12	1906	7	1.76	<5	8	203	<5	0.03	<10	<10	189	<10	92	2
130196	0.9	2.14	150	70	<0.5	<5	5.59	2	27	56	201	5.56	<1	0.10	<10	2.09	1705	<2	0.02	12	1961	8	1.60	<5	9	127	<5	0.04	<10	10	154	<10	92	2
130197	0.3	2.11	248	59	<0.5	6	7.76	5	27	55	81	5.47	<1	0.07	<10	2.20	1950	<2	0.01	13	1580	8	1.78	<5	9	152	<5	0.02	<10	10	156	<10	97	2
130198	0.7	2.79	189	54	<0.5	6	5.25	3	33	66	89	6.88	<1	0.06	<10	3.02	1770	<2	0.01	17	1687	10	2.28	<5	10	108	<5	0.03	<10	10	185	<10	120	3
130199	<0.2	2.08	12	72	<0.5	<5	4.36	<1	19	6	35	5.11	<1	0.15	<10	1.52	2084	<2	0.01	3	1786	14	0.12	<5	3	124	<5	0.04	<10	13	62	<10	95	2
130200	<0.2	0.84	8	245	<0.5	<5	0.54	<1	8	78	4	2.19	<1	0.31	<10	0.65	585	<2	0.04	6	817	4	0.05	<5	2	31	<5	0.11	<10	<10	39	<10	55	1
130201	<0.2	2.03	10	71	<0.5	<5	2.94	<1	19	5	16	5.23	<1	0.14	<10	1.49	2070	<2	0.01	3	1767	18	0.08	<5	2	95	<5	0.04	<10	13	57	<10	109	2
130202	<0.2	1.88	8	79	<0.5	<5	2.42	<1	18	8	25	5.01	<1	0.15	<10	1.32	2008	<2	0.01	3	1688	24	0.08	<5	3	82	<5	0.05	<10	12	53	<10	125	2
130203	0.2	2.03	36	83	<0.5	<5	2.38	<1	20	13	40	5.60	<1	0.15	<10	1.48	2167	<2	0.01	3	1635	29	0.42	<5	2	87	<5	0.03	<10	13	56	<10	106	2
130204	0.2	2.32	24	61	<0.5	<5	3.36	<1	22	9	46	5.83	<1	0.16	10	1.81	2884	<2	<0.01	4	1773	48	0.39	<5	2	101	<5	0.03	<10	17	53	<10	137	2
130205	0.3	2.14	43	54	<0.5	<5	3.05	<1	21	7	52	6.11	<1	0.13	<10	1.66	2379	<2	0.01	4	1782	17	1.22	<5	3	73	<5	0.06	<10	17	62	<10	108	2
130206	0.4	1.93	126	81	<0.5	<5	6.75	2	18	10	17	5.24	<1	0.12	<10	1.54	3472	<2	0.01	3	1608	22	0.86	<5	3	136	<5	0.05	<10	19	54	<10	90	2
130207	0.4	1.55	157	68	<0.5	<5	5.05	3	20	8	33	5.17	<1	0.15	<10	1.25	3067	<2	<0.01	3	1734	25	2.08	<5	2	84	<5	0.05	<10	18	36	<10	75	2
130208	<0.2	1.39	29	65	<0.5	<5	7.76	<1	15	24	11	3.94	<1	0.14	<10	1.09	3106	<2	<0.01	3	1383	12	0.95	<5	2	475	<5	0.05	<10	18	30	<10	65	1
130209	0.3	1.68	40	95	<0.5	<5	4.45	<1	20	5	54	4.90	<1	0.16	<10	1.28	2705	<2	<0.01	3	1652	36	1.30	<5	2	98	<5	0.05	<10	16	36	<10	108	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3497RJ

Date : Oct-09-08

Ascot Resources Ltd

Attention: Sue Dean

Project: Dilworth/shipment 29

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130210	0.2	1.83	25	70	<0.5	<5	4.02	<1	21	11	55	5.01	<1	0.17	<10	1.34	2752	<2	<0.01	4	1905	19	0.82	<5	2	101	<5	0.05	<10	17	43	<10	96	2
130211	<0.2	1.79	23	87	<0.5	<5	3.15	<1	20	12	24	4.88	<1	0.20	<10	1.42	2481	<2	<0.01	4	1717	11	1.27	<5	2	103	<5	0.07	<10	15	45	<10	74	2
130212	0.3	1.98	83	116	<0.5	<5	5.17	1	21	16	22	4.83	<1	0.28	<10	1.40	3018	<2	0.01	3	1660	15	1.40	<5	3	127	<5	0.13	<10	15	53	<10	81	3
130213	<0.2	2.05	53	118	<0.5	<5	5.41	<1	21	23	9	4.54	<1	0.34	<10	1.30	2683	<2	0.01	3	1662	10	1.21	<5	3	192	<5	0.15	<10	14	50	<10	57	3
130214	<0.2	1.96	23	89	<0.5	<5	2.79	<1	22	13	34	4.72	<1	0.21	<10	1.41	2053	<2	0.01	3	1715	7	1.13	<5	3	140	<5	0.17	<10	10	57	<10	65	4
130215	<0.2	2.03	25	95	<0.5	<5	2.93	<1	21	23	38	4.40	<1	0.22	<10	1.38	2044	<2	0.01	4	1678	4	0.95	<5	3	155	<5	0.17	<10	<10	55	<10	61	6
130216	<0.2	2.05	24	100	<0.5	<5	3.34	<1	21	18	53	4.50	<1	0.22	<10	1.30	2229	<2	0.01	3	1836	4	0.91	<5	3	188	<5	0.18	<10	11	60	<10	60	6
130217	<0.2	2.31	22	63	<0.5	<5	3.43	<1	22	17	20	4.79	<1	0.20	<10	1.63	2320	<2	0.01	4	1735	4	0.66	<5	3	176	<5	0.16	<10	13	55	<10	69	6
130218	<0.2	2.19	33	75	<0.5	<5	2.83	<1	24	19	11	4.72	<1	0.17	<10	1.57	2158	<2	0.01	4	1824	7	0.74	<5	3	157	<5	0.17	<10	12	56	<10	83	6
130219	0.2	2.16	35	102	<0.5	<5	5.49	<1	20	17	58	4.60	<1	0.21	<10	1.47	3066	<2	0.01	3	1711	9	0.78	<5	4	198	<5	0.18	<10	15	63	<10	99	5
130220	<0.2	2.22	9	101	<0.5	<5	3.20	<1	22	15	58	4.75	<1	0.19	<10	1.50	2319	<2	0.01	4	1740	12	0.49	<5	4	158	<5	0.17	<10	13	64	<10	111	5
130221	0.2	2.25	31	106	<0.5	<5	3.85	<1	24	15	49	5.24	<1	0.28	<10	1.38	2879	<2	0.01	4	1873	18	1.24	<5	4	167	<5	0.19	<10	14	58	<10	111	5
130222	0.3	2.15	20	108	<0.5	<5	4.81	1	22	13	67	4.82	<1	0.30	10	1.29	3092	<2	0.01	3	1664	22	0.93	<5	4	148	<5	0.17	<10	14	55	<10	113	3
130223	0.2	1.72	85	108	<0.5	<5	5.62	1	19	16	33	4.55	<1	0.28	<10	1.10	3037	<2	<0.01	3	1568	14	1.67	<5	3	163	<5	0.14	<10	14	46	<10	65	3
130224	<0.2	2.13	10	89	<0.5	<5	3.21	<1	20	14	47	4.57	<1	0.22	<10	1.35	2426	<2	0.01	3	1656	3	0.49	<5	4	168	<5	0.17	<10	13	61	<10	74	4
130225	>200.0	0.63	597	182	<0.5	105	0.56	21	7	21	7456	2.42	6	0.11	<10	0.60	296	558	0.03	5	539	940	1.24	1708	1	72	<5	0.06	<10	<10	19	<10	960	2
130226	1.3	2.22	14	90	<0.5	<5	4.24	<1	21	17	60	4.65	<1	0.21	<10	1.33	2623	<2	0.01	3	1800	6	0.43	<5	4	178	<5	0.18	<10	14	61	<10	85	5
130227	0.5	2.14	26	83	<0.5	<5	3.89	<1	22	23	65	4.90	<1	0.22	<10	1.43	2471	<2	0.01	4	1764	8	0.92	<5	4	158	<5	0.15	<10	13	58	<10	89	5
130228	0.5	2.41	53	148	<0.5	<5	5.73	1	25	12	35	4.86	<1	0.25	<10	1.54	3072	<2	0.01	3	1799	14	0.81	<5	4	241	<5	0.17	<10	15	55	<10	81	6
130229	0.4	1.96	49	94	<0.5	<5	4.75	1	19	14	39	4.25	<1	0.23	<10	1.15	2462	<2	0.01	3	1572	38	0.73	<5	3	147	<5	0.16	<10	12	55	<10	104	4
130230	0.5	2.09	96	97	<0.5	<5	3.43	2	21	14	57	5.20	<1	0.25	<10	1.36	2403	<2	0.01	4	1765	23	1.05	<5	3	82	<5	0.16	<10	<10	58	<10	105	3
130231	0.2	2.00	60	94	<0.5	<5	4.59	1	22	13	41	5.12	<1	0.24	<10	1.17	2394	<2	0.01	3	1749	21	1.34	<5	3	143	<5	0.15	<10	12	52	<10	110	4
130232	<0.2	2.24	11	87	<0.5	<5	3.21	<1	21	13	48	5.00	<1	0.20	<10	1.45	1865	<2	0.02	3	1736	6	0.38	<5	3	138	<5	0.18	<10	<10	58	<10	112	4
130233	<0.2	2.19	<5	85	<0.5	<5	4.08	<1	21	13	50	4.70	<1	0.19	<10	1.49	1869	<2	0.02	3	1794	14	0.17	<5	4	151	<5	0.17	<10	<10	62	12	115	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Quality Assaying for over 25 Years

Assay Certificate

8V-3498-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 30**
Attn: **Sue Dean**

Oct-10-08

We hereby certify the following assay of 22 core samples submitted Sep-29-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130234	0.01	<0.01	0.2
130235	<0.01		<0.1
130236	<0.01		0.2
130237	0.01		0.1
130238	<0.01		<0.1
130239	<0.01		0.3
130240	0.01		0.4
130241	0.01		0.4
130242	0.02		0.4
130243	0.01	0.01	0.6
130244	0.01		0.2
130245	0.02		0.3
130246	0.02		0.3
130247	0.01		0.2
130248	0.01		0.3
130249	0.01		0.3
130250	<0.01		<0.1
130251	0.01		0.4
130252	0.01		0.3
130253	<0.01	0.01	0.2
130254	0.01		0.3
130255	0.01		0.4
*0211	2.19		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3498-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 30**
Attn: **Sue Dean**

Oct-10-08

We hereby certify the following assay of 22 core samples submitted Sep-29-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130256	0.01	0.01	<0.1
130257	0.01		<0.1
130258	0.01		<0.1
130259	<0.01		<0.1
130260	0.01		<0.1
130261	0.01		0.2
130262	0.03		0.2
130263	0.02		0.2
130264	0.02		<0.1
130265	0.01	<0.01	<0.1
130266	0.06		0.2
130267	0.02		<0.1
130268	0.01		<0.1
130269	0.06		0.4
130270	0.02		<0.1
130271	<0.01		<0.1
130272	0.01		<0.1
130273	0.01		<0.1
130274	0.05		1.0
130275	0.50	0.46	<0.1
130276	0.06		0.8
130277	0.26		2.0
*0211	2.21		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3498-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 30**
Attn: **Sue Dean**

Oct-10-08

We hereby certify the following assay of 22 core samples submitted Sep-29-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
130278	0.23	0.24	2.3	
130279	0.15		4.3	
130280	0.25		5.6	
130281	0.16		2.7	
130282	0.12		2.3	
130283	0.16		3.0	
130284	0.16		3.2	
130285	0.18		2.7	
130286	0.15		2.3	
130287	0.25	0.25	1.5	
130288	0.25		2.1	
130289	0.20		2.1	
130290	0.17		2.3	
130291	0.17		5.8	
121535	0.18		7.1	1.53
121536	0.30		3.9	
121537	0.36		1.3	
121538	0.08		1.0	
121539	0.32		11.2	2.61
121540	0.18	0.18	1.7	
121541	0.14		3.8	
121542	0.07		0.7	
*0211	2.18			
*CCu-1c				3.96
*BLANK	<0.01			<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3498-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 30**
Attn: **Sue Dean**

Oct-10-08

We hereby certify the following assay of 22 core samples submitted Sep-29-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121543	0.06	0.06	1.6
121544	0.11		12.3
121545	0.03		3.1
121546	0.02		1.5
121547	0.03		1.8
121548	0.02		1.5
121549	0.02		2.6
121550	<0.01		<0.1
121551	0.02		2.4
121552	0.05	0.04	1.8
121553	0.02		1.3
121554	0.02		1.3
121555	0.19		2.2
121556	0.01		1.3
121557	0.02		4.8
121558	0.16		4.1
121559	0.35		5.7
121560	0.04		3.3
121561	0.01		4.3
121562	0.01	0.01	1.9
121563	0.02		1.6
121564	<0.01		0.8
*0211	2.24		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3498-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 30**
Attn: **Sue Dean**

Oct-10-08

We hereby certify the following assay of 22 core samples submitted Sep-29-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121565	0.01	<0.01	0.4
121566	0.01		2.2
121567	0.01		0.8
121568	<0.01		0.6
121569	0.02		2.9
121570	0.02		3.1
121571	0.03		3.4
121572	0.02		0.2
121573	0.03		1.6
121574	0.02	0.01	0.3
121575	1.79		158
121576	0.01		<0.1
121577	0.01		<0.1
121578	0.01		<0.1
121579	0.02		<0.1
121580	<0.01		<0.1
121581	0.01		<0.1
121582	0.01		<0.1
121583	0.03		1.4
121584	0.01	0.01	<0.1
121585	0.02		0.1
121586	0.03		<0.1
*0211	2.23		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3498-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 30**
Attn: **Sue Dean**

Oct-10-08

We hereby certify the following assay of 22 core samples submitted Sep-29-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121587	0.01	0.01	0.2
121588	0.02		0.2
121589	0.02		<0.1
121590	0.01		<0.1
121591	0.02		<0.1
121592	0.01		0.1
121593	<0.01		0.3
121594	0.01		<0.1
121595	<0.01		<0.1
121596	0.04	0.03	2.1
121597	0.08		1.0
121598	0.07		0.9
121599	0.02		1.5
121600	<0.01		<0.1
121601	0.02		1.4
121602	0.01		1.7
121603	0.01		1.6
121604	0.01		2.0
121605	0.02		3.0
121606	0.03	0.02	0.6
121607	0.03		1.4
121608	0.01		<0.1
*0211	2.19		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3498-RA7

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 30**
Attn: **Sue Dean**

Oct-10-08

We hereby certify the following assay of 8 core samples submitted Sep-29-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121609	0.02	0.02	0.2
121610	<0.01		0.3
121611	0.01		0.2
121612	0.01		<0.1
121613	<0.01		<0.1
121614	0.06		0.4
121615	<0.01		<0.1
121616	0.04		1.1
*0211	2.21		
*BLANK	<0.01		

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3498RJ**

Date : Oct-10-08

Ascot Resources Ltd

Attention: Sue Dean

Project: Dilworth/shipment 30

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130234	0.2	2.28	<5	77	<0.5	<5	4.09	<1	18	10	47	4.51	<1	0.25	<10	1.46	1772	<2	0.03	3	1566	13	0.12	<5	3	193	<5	0.11	<10	11	56	<10	108	4
130235	<0.2	2.14	<5	51	<0.5	<5	4.33	<1	18	15	29	4.14	1	0.15	<10	1.41	1516	<2	0.04	3	1594	6	0.06	<5	4	206	<5	0.13	<10	<10	61	<10	91	5
130236	0.2	2.05	<5	59	<0.5	<5	2.19	<1	20	9	40	4.42	<1	0.17	<10	1.39	1359	<2	0.03	3	1577	10	0.02	<5	3	102	<5	0.13	<10	<10	56	<10	116	4
130237	<0.2	1.99	<5	88	<0.5	<5	3.15	<1	18	9	44	4.27	<1	0.21	<10	1.23	1475	<2	0.03	3	1547	10	0.07	<5	3	128	<5	0.12	<10	10	56	<10	107	4
130238	<0.2	1.87	<5	123	<0.5	<5	4.40	<1	18	7	20	4.55	<1	0.23	<10	0.91	1823	<2	0.03	3	1658	7	0.29	<5	4	148	<5	0.13	<10	<10	60	<10	95	5
130239	0.3	2.06	7	135	<0.5	<5	2.78	<1	21	6	51	4.55	<1	0.36	<10	1.03	1728	<2	0.02	3	1564	16	0.42	<5	3	95	<5	0.14	<10	11	51	<10	92	4
130240	0.4	1.86	20	150	<0.5	<5	3.96	<1	17	6	53	3.73	<1	0.36	10	0.99	2330	<2	0.01	2	1571	25	0.25	<5	3	119	<5	0.13	<10	13	37	<10	73	3
130241	0.4	1.57	26	106	<0.5	<5	3.67	<1	15	6	53	3.45	<1	0.36	<10	0.81	2283	13	0.01	2	1401	23	0.67	<5	2	105	<5	0.07	<10	12	29	<10	65	2
130242	0.4	1.81	46	90	<0.5	<5	4.76	1	19	9	29	3.98	<1	0.38	<10	0.90	2850	2	0.01	3	1484	16	0.98	<5	3	144	<5	0.14	<10	16	37	<10	52	3
130243	0.6	1.65	41	79	<0.5	<5	6.88	1	20	5	36	3.94	<1	0.37	<10	0.89	2860	2	0.01	2	1537	111	1.11	<5	3	124	<5	0.14	<10	15	39	<10	88	2
130244	0.2	1.74	13	93	<0.5	<5	4.69	<1	17	9	21	3.70	<1	0.39	<10	0.90	2307	<2	0.01	3	1570	9	0.50	<5	4	165	<5	0.14	<10	12	40	10	53	3
130245	0.3	1.58	60	90	<0.5	<5	4.39	1	19	7	29	4.15	<1	0.32	<10	0.89	2567	<2	0.01	2	1539	16	1.51	<5	4	148	<5	0.15	<10	14	45	<10	49	4
130246	0.3	2.11	37	71	<0.5	<5	3.26	1	21	8	28	4.82	<1	0.26	<10	1.36	2552	<2	0.02	3	1593	10	0.88	<5	5	146	<5	0.18	<10	15	62	<10	79	5
130247	0.2	2.22	<5	75	<0.5	<5	2.98	<1	22	9	37	4.62	<1	0.21	<10	1.46	2151	<2	0.03	3	1678	7	0.32	<5	5	163	<5	0.19	<10	10	74	<10	82	6
130248	0.3	2.34	<5	59	<0.5	<5	2.85	<1	23	8	63	4.99	<1	0.21	<10	1.60	2334	<2	0.03	3	1762	5	0.26	<5	5	152	<5	0.16	<10	11	81	<10	93	5
130249	0.3	2.39	5	69	<0.5	<5	3.45	<1	23	4	35	4.93	<1	0.27	<10	1.71	2648	<2	0.01	3	1684	24	0.44	<5	5	130	<5	0.18	<10	14	62	<10	106	4
130250	<0.2	1.00	<5	263	<0.5	<5	0.54	<1	9	65	1	2.09	<1	0.51	<10	0.63	619	<2	0.06	5	811	3	0.01	<5	3	48	<5	0.16	<10	<10	42	<10	51	2
130251	0.4	2.44	31	109	<0.5	<5	3.98	1	26	5	51	5.40	<1	0.31	11	1.80	2903	<2	0.02	3	1830	16	0.73	<5	5	119	<5	0.21	<10	14	75	<10	141	4
130252	0.3	2.32	34	92	<0.5	<5	3.30	<1	23	8	33	5.19	<1	0.29	10	1.58	2461	<2	0.02	3	1652	8	0.61	<5	5	114	<5	0.17	<10	12	74	<10	93	3
130253	0.2	2.11	19	70	<0.5	<5	5.21	<1	17	5	27	4.56	<1	0.29	10	1.41	2232	<2	0.01	3	1631	9	0.38	<5	4	147	<5	0.06	<10	13	61	<10	91	2
130254	0.3	2.36	25	72	<0.5	<5	3.53	<1	23	5	44	5.41	<1	0.22	<10	1.72	2328	<2	0.02	3	1639	12	0.46	<5	4	96	<5	0.13	<10	12	70	<10	110	3
130255	0.4	2.39	12	81	<0.5	<5	3.63	<1	24	5	57	5.22	<1	0.31	<10	1.72	2462	<2	0.01	4	1737	26	0.55	<5	5	120	<5	0.15	<10	13	73	<10	124	3
130256	<0.2	2.65	<5	76	<0.5	<5	3.42	<1	25	7	47	5.60	<1	0.28	<10	1.76	2252	<2	0.02	4	1780	7	0.25	<5	6	136	<5	0.16	<10	14	87	<10	103	4
130257	<0.2	2.54	<5	71	<0.5	<5	3.63	<1	25	4	40	5.49	<1	0.26	<10	1.77	2315	<2	0.02	4	1779	13	0.32	<5	5	143	<5	0.15	<10	13	79	<10	111	4
130258	<0.2	2.34	<5	62	<0.5	<5	3.54	<1	23	5	44	4.99	<1	0.21	<10	1.76	2150	<2	0.02	3	1756	13	0.31	<5	5	127	<5	0.16	<10	12	81	<10	108	4
130259	<0.2	2.59	<5	56	<0.5	<5	3.50	<1	25	4	40	5.87	<1	0.18	<10	1.89	2165	<2	0.02	4	1744	3	0.22	<5	7	113	<5	0.20	<10	13	99	<10	95	4
130260	<0.2	2.36	16	76	<0.5	<5	4.66	<1	22	5	38	5.05	<1	0.28	<10	1.60	2566	<2	0.01	3	1582	13	0.52	<5	5	142	<5	0.18	<10	15	73	<10	85	4
130261	0.2	2.46	24	71	<0.5	<5	3.71	<1	24	4	40	5.47	<1	0.29	<10	1.69	2648	<2	0.02	4	1665	14	0.54	<5	5	104	<5	0.18	<10	11	81	<10	97	3
130262	0.2	2.34	64	82	<0.5	<5	4.10	1	22	5	33	5.27	<1	0.30	10	1.59	2906	<2	0.01	3	1688	14	0.70	<5	5	110	<5	0.18	<10	15	77	<10	79	3
130263	0.2	2.38	47	85	<0.5	<5	4.24	1	23	4	49	5.55	<1	0.31	10	1.56	2795	<2	0.01	3	1708	14	0.90	<5	5	130	<5	0.18	<10	15	79	<10	99	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3498RJ

Date : Oct-10-08

Ascot Resources Ltd

Attention: Sue Dean

Project: Dilworth/shipment 30

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130264	<0.2	2.34	40	75	<0.5	<5	4.22	1	21	6	34	5.20	<1	0.30	<10	1.55	2216	<2	0.02	3	1696	10	0.54	<5	5	116	<5	0.15	<10	14	72	<10	82	3
130265	<0.2	2.34	20	75	<0.5	<5	6.16	<1	19	4	44	5.00	<1	0.34	12	1.50	2462	<2	0.02	3	1615	<2	0.40	<5	5	137	<5	0.08	<10	14	66	<10	71	2
130266	0.2	1.69	166	85	<0.5	<5	5.79	4	16	9	21	4.02	<1	0.37	10	1.03	2418	<2	0.01	2	1520	18	1.37	<5	4	139	<5	0.09	<10	<10	46	<10	46	2
130267	<0.2	2.26	81	94	<0.5	<5	5.72	2	20	6	23	4.98	<1	0.44	11	1.37	2615	<2	0.02	3	1785	31	0.84	<5	4	134	<5	0.13	<10	14	58	<10	70	3
130268	<0.2	2.32	47	86	<0.5	<5	4.50	1	21	7	34	5.43	<1	0.36	<10	1.53	2468	<2	0.02	3	1761	31	1.06	<5	4	122	<5	0.07	<10	10	68	<10	98	3
130269	0.4	1.86	111	76	<0.5	5	7.81	3	18	6	38	4.75	<1	0.31	<10	1.33	3061	<2	0.01	3	1585	77	1.46	<5	5	204	<5	0.01	<10	17	58	<10	201	2
130270	<0.2	2.38	18	75	<0.5	<5	5.78	<1	26	6	34	5.15	<1	0.32	<10	1.56	2483	12	0.02	4	1765	5	0.49	<5	5	134	<5	0.09	<10	14	78	<10	90	3
130271	<0.2	2.02	6	80	<0.5	<5	4.23	<1	17	7	29	4.34	<1	0.31	11	1.25	2191	<2	0.02	2	1647	<2	0.22	<5	4	134	<5	0.11	<10	<10	61	<10	69	3
130272	<0.2	1.98	12	90	<0.5	<5	5.19	<1	17	5	26	4.59	<1	0.27	11	1.21	2104	<2	0.03	2	1519	<2	0.38	<5	4	161	<5	0.04	<10	<10	60	<10	69	2
130273	<0.2	2.28	39	91	<0.5	<5	4.81	<1	21	5	42	5.02	<1	0.34	10	1.51	2359	<2	0.02	2	1723	13	0.50	<5	4	138	<5	0.01	<10	<10	66	<10	97	2
130274	1.0	1.95	84	91	<0.5	<5	4.29	3	19	5	45	5.18	<1	0.33	<10	1.21	2806	<2	0.01	3	1613	222	1.53	<5	3	108	<5	0.01	<10	16	58	<10	357	2
130275	<0.2	1.09	6838	25	<0.5	16	6.33	166	185	15	71	3.88	<1	0.06	13	0.25	826	15	0.09	33	1400	9	1.39	<5	2	97	<5	0.07	<10	<10	44	<10	91	12
130276	0.8	0.98	148	254	<0.5	<5	5.30	4	14	10	19	3.51	<1	0.34	<10	0.61	3341	<2	0.01	2	1083	56	1.41	<5	2	129	<5	<0.01	<10	14	29	<10	109	1
130277	2.0	1.12	3385	127	<0.5	<5	5.29	81	13	17	5	3.77	<1	0.38	<10	0.59	4025	<2	0.01	3	979	405	2.28	<5	2	140	<5	<0.01	<10	17	29	<10	161	1
130278	2.3	1.16	3421	88	<0.5	5	4.83	87	14	30	23	3.94	<1	0.16	<10	0.86	3835	<2	0.01	3	995	316	2.48	<5	2	131	<5	<0.01	<10	18	53	<10	153	1
130279	4.3	2.03	1072	79	<0.5	6	5.38	31	26	97	104	4.97	<1	0.12	<10	1.86	4667	4	0.01	17	1253	603	2.22	<5	9	128	<5	0.01	<10	23	120	11	631	1
130280	5.6	1.83	2511	74	<0.5	8	4.60	70	31	97	126	6.52	<1	0.14	<10	1.64	4268	<2	0.01	21	1425	716	4.81	<5	8	117	<5	<0.01	<10	24	118	18	1178	2
130281	2.7	1.00	471	64	<0.5	7	5.79	12	24	52	49	5.77	1	0.17	<10	0.84	3685	<2	0.01	15	1314	54	>5.00	<5	5	141	<5	<0.01	<10	20	63	<10	93	2
130282	2.3	1.12	374	77	<0.5	8	6.67	10	25	67	27	5.56	<1	0.19	<10	0.89	4011	<2	0.01	17	1499	298	>5.00	<5	5	199	<5	<0.01	<10	21	65	<10	245	1
130283	3.0	1.49	337	71	<0.5	7	6.04	10	32	89	181	5.61	1	0.18	<10	1.42	3491	<2	0.01	25	1621	130	4.36	<5	8	187	<5	0.01	<10	17	83	<10	306	2
130284	3.2	1.40	455	79	<0.5	8	6.30	11	34	100	120	6.29	4	0.19	<10	1.63	3570	<2	0.01	25	1679	37	>5.00	<5	7	194	<5	<0.01	<10	20	99	<10	89	2
130285	2.7	1.20	491	83	<0.5	7	4.84	12	27	72	85	5.69	1	0.19	<10	1.59	3009	<2	0.01	21	1450	176	4.50	<5	7	148	<5	0.01	<10	18	73	<10	96	2
130286	2.3	1.69	651	92	<0.5	8	4.13	16	35	86	83	6.03	<1	0.19	<10	3.07	2607	<2	0.01	23	1758	31	3.64	<5	9	168	<5	<0.01	<10	18	132	<10	129	2
130287	1.5	2.50	644	89	<0.5	8	4.48	16	29	110	95	5.91	<1	0.12	<10	3.46	2333	<2	0.01	21	1636	10	2.33	<5	12	164	<5	<0.01	<10	15	146	<10	64	2
130288	2.1	1.19	472	26	<0.5	8	2.66	11	47	77	65	7.22	<1	0.22	<10	1.95	1524	<2	0.01	48	1714	16	>5.00	<5	7	106	<5	<0.01	<10	13	76	<10	67	3
130289	2.1	0.85	507	66	<0.5	7	3.37	12	30	54	49	5.50	<1	0.23	<10	1.54	1446	<2	0.01	30	1446	16	>5.00	<5	6	122	<5	<0.01	<10	10	54	<10	52	2
130290	2.3	1.01	538	90	<0.5	7	4.71	13	40	74	36	4.41	<1	0.22	<10	1.25	1586	<2	0.01	36	1164	18	4.13	<5	6	143	<5	<0.01	<10	13	51	<10	42	2
130291	5.8	1.64	553	86	<0.5	8	3.70	14	38	95	159	5.49	<1	0.23	<10	2.01	1990	<2	0.01	27	1680	80	4.50	<5	7	130	<5	<0.01	<10	13	96	<10	123	2
121535	7.1	0.75	572	46	<0.5	9	5.58	138	14	43	374	6.75	<1	0.12	<10	0.53	3195	2	0.01	3	771	2631	>5.00	<5	2	166	<5	0.01	<10	25	34	254	>10000	2
121536	3.9	0.85	263	91	<0.5	7	7.07	44	9	38	52	4.33	<1	0.17	<10	0.54	3399	4	0.01	2	901	3517	4.01	<5	2	145	<5	0.01	<10	16	33	68	4214	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3498RJ

Date : Oct-10-08

Ascot Resources Ltd

Attention: Sue Dean

Project: Dilworth/shipment 30

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121537	1.3	1.04	163	117	<0.5	<5	5.29	5	10	29	27	3.28	<1	0.24	<10	0.59	3227	3	0.01	2	961	376	1.96	<5	2	110	<5	0.01	<10	17	35	<10	231	1
121538	1.0	1.47	146	107	<0.5	<5	2.95	9	14	16	40	4.09	<1	0.30	<10	0.92	2962	9	0.01	2	1205	146	2.00	<5	2	65	<5	0.04	<10	16	46	12	710	1
121539	11.2	1.16	407	41	<0.5	10	3.97	241	16	43	498	8.14	1	0.12	<10	0.83	3286	23	0.01	2	685	4843	>5.00	<5	2	88	<5	0.02	<10	26	47	458	>10000	3
121540	1.7	1.28	259	51	<0.5	5	4.79	26	12	26	43	5.10	<1	0.10	<10	1.00	3543	33	0.01	1	834	399	3.79	<5	2	100	<5	0.04	<10	19	49	39	2491	1
121541	3.8	1.43	214	57	<0.5	7	6.33	77	14	23	142	5.60	<1	0.11	<10	1.10	3994	2	0.01	2	847	1229	4.33	<5	3	114	<5	0.02	<10	21	56	134	8055	1
121542	0.7	1.04	121	112	<0.5	<5	5.04	4	7	19	16	2.71	<1	0.27	<10	0.56	2821	<2	0.01	1	1110	71	1.19	<5	2	110	<5	<0.01	<10	14	21	<10	231	1
121543	1.6	1.13	133	89	<0.5	5	6.93	5	8	32	25	3.14	<1	0.17	<10	0.82	4026	2	0.01	1	874	272	1.57	<5	3	122	<5	0.01	<10	16	36	<10	375	2
121544	12.3	3.01	157	43	<0.5	<5	6.41	13	32	205	301	6.85	<1	0.15	<10	3.08	7567	<2	0.01	31	1677	2619	3.40	<5	15	132	<5	0.08	<10	42	145	44	2715	1
121545	3.1	2.34	85	54	<0.5	<5	7.80	3	29	195	195	5.04	<1	0.12	<10	2.12	6837	<2	0.01	32	1374	386	1.37	<5	13	132	<5	0.05	<10	35	109	10	416	1
121546	1.5	2.18	49	44	<0.5	<5	7.36	2	33	214	34	3.82	<1	0.12	<10	1.81	6495	<2	0.01	37	1621	226	0.54	<5	14	186	<5	0.07	<10	34	113	17	484	3
121547	1.8	2.47	48	41	<0.5	<5	8.62	1	34	252	91	4.93	<1	0.07	<10	2.41	7040	<2	0.01	39	1809	149	1.06	<5	14	229	<5	0.09	<10	33	172	<10	221	3
121548	1.5	2.44	48	36	<0.5	<5	9.62	2	33	249	41	4.85	<1	0.10	<10	2.30	6596	<2	0.01	37	1577	160	0.67	<5	19	160	<5	0.07	<10	30	172	<10	281	1
121549	2.6	2.57	47	40	<0.5	<5	7.77	3	37	281	120	4.69	<1	0.07	<10	2.60	7570	<2	0.01	42	1888	463	0.73	<5	18	162	<5	0.10	<10	35	178	12	624	2
121550	<0.2	1.09	<5	257	<0.5	<5	1.00	<1	10	96	2	2.21	<1	0.49	<10	0.74	992	<2	0.08	7	903	13	0.02	<5	3	55	<5	0.15	<10	<10	48	<10	74	2
121551	2.4	2.33	53	53	<0.5	<5	9.48	2	34	308	191	5.17	<1	0.06	<10	2.34	6130	<2	0.01	39	1893	170	1.17	<5	24	166	<5	0.08	<10	25	216	<10	257	2
121552	1.8	2.21	66	48	<0.5	<5	8.48	2	35	252	110	4.85	<1	0.05	<10	2.34	5367	<2	0.01	40	1785	65	1.43	<5	13	214	<5	0.08	<10	22	156	<10	140	3
121553	1.3	1.51	49	44	<0.5	<5	7.62	1	34	228	142	3.37	<1	0.05	<10	1.60	3884	<2	0.01	33	1825	31	1.13	<5	10	184	<5	0.11	<10	14	125	<10	70	4
121554	1.3	1.92	70	48	<0.5	<5	7.90	1	40	244	71	4.41	<1	0.04	<10	1.95	4856	<2	0.01	43	1863	67	1.43	<5	13	189	<5	0.10	<10	20	152	<10	99	4
121555	2.2	1.80	1103	35	<0.5	<5	8.66	33	27	163	168	3.92	<1	0.06	<10	1.49	4944	<2	0.01	28	1324	446	1.08	<5	10	215	<5	0.07	<10	21	107	14	871	3
121556	1.3	1.87	72	134	<0.5	<5	8.50	2	30	179	18	4.02	<1	0.12	<10	1.39	6550	<2	0.01	32	1546	93	0.31	<5	12	183	<5	0.05	<10	29	109	<10	148	2
121557	4.8	2.72	112	54	<0.5	5	9.72	12	33	247	150	5.73	<1	0.11	<10	2.31	8090	<2	0.01	40	1770	1188	1.17	<5	19	169	<5	0.06	<10	43	176	28	1590	2
121558	4.1	2.42	1942	40	<0.5	6	9.36	63	28	250	161	5.44	<1	0.07	<10	2.11	7053	<2	0.01	34	1561	1130	1.50	<5	21	146	<5	0.04	<10	35	181	29	1783	1
121559	5.7	3.14	6306	37	<0.5	8	8.35	189	27	246	204	6.42	<1	0.08	<10	2.88	8437	5	0.01	35	1552	2318	1.50	8	20	151	<5	0.03	<10	46	189	60	3542	1
121560	3.3	2.47	141	42	<0.5	6	12.75	7	25	227	24	4.95	<1	0.06	<10	2.09	9409	8	0.01	32	1457	891	1.09	<5	18	170	<5	0.06	<10	52	141	18	1003	1
121561	4.3	2.00	97	247	<0.5	<5	9.35	7	33	226	117	4.11	<1	0.06	<10	1.99	8949	4	0.01	33	1777	1308	0.95	<5	13	154	<5	0.10	<10	43	141	26	1400	4
121562	1.9	2.07	59	155	<0.5	7	9.99	2	30	185	118	4.71	<1	0.19	<10	1.94	6752	20	0.01	33	1567	206	0.14	<5	18	212	<5	0.01	<10	32	137	<10	287	1
121563	1.6	2.02	36	363	<0.5	<5	8.37	1	36	251	197	4.18	<1	0.14	<10	3.14	5125	4	0.01	39	1755	91	0.32	<5	22	346	<5	0.07	<10	20	153	<10	97	5
121564	0.8	2.31	24	247	<0.5	<5	8.07	<1	27	198	2	3.08	<1	0.04	<10	2.85	5875	<2	0.01	29	1751	93	0.01	<5	9	195	<5	0.10	<10	22	107	<10	61	7
121565	0.4	1.62	42	133	<0.5	<5	6.13	1	30	173	52	2.70	<1	0.05	<10	1.89	3756	3	0.01	29	1748	54	0.18	<5	6	165	<5	0.12	<10	13	91	<10	38	7
121566	2.3	2.10	58	113	<0.5	<5	9.88	1	38	267	248	4.06	<1	0.07	<10	2.23	5242	4	0.01	41	1795	14	0.34	<5	14	216	<5	0.11	<10	22	160	<10	40	5

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3498RJ

Date : Oct-10-08

Ascot Resources Ltd

Attention: Sue Dean

Project: Dilworth/shipment 30

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121567	0.8	1.79	47	155	<0.5	<5	>15.00	3	24	185	2	3.86	<1	0.03	<10	1.15	6000	<2	0.01	27	1344	399	0.47	<5	19	186	<5	0.08	<10	28	120	<10	411	6
121568	0.6	2.05	44	227	<0.5	<5	13.59	1	32	195	2	4.36	<1	0.05	<10	1.47	6647	6	0.01	30	1683	35	0.16	<5	15	283	<5	0.11	<10	26	136	<10	60	7
121569	3.1	1.93	71	119	<0.5	<5	8.81	8	36	210	94	4.38	<1	0.05	<10	1.83	5777	4	0.01	33	1797	959	0.74	<5	14	222	<5	0.14	<10	26	161	25	1515	7
121570	3.3	2.45	106	59	<0.5	<5	10.13	3	43	279	282	5.59	<1	0.06	<10	2.57	6390	2	0.01	42	1829	191	1.46	<5	18	223	<5	0.11	<10	27	195	<10	301	4
121571	3.6	2.55	255	55	<0.5	<5	13.22	16	29	220	103	5.14	<1	0.13	<10	2.11	7473	2	0.01	29	1513	951	0.73	<5	19	257	<5	0.08	<10	33	158	26	1643	3
121572	0.2	1.73	58	91	<0.5	<5	3.68	2	11	44	24	3.96	<1	0.27	12	1.20	2515	2	0.01	3	1130	56	0.72	<5	5	77	<5	0.02	<10	<10	69	<10	125	3
121573	1.7	1.45	276	75	<0.5	<5	5.29	10	13	69	48	3.73	<1	0.25	<10	1.13	2976	2	0.01	9	1101	760	0.88	<5	6	105	<5	0.02	<10	15	65	11	690	3
121574	0.3	0.82	58	132	<0.5	<5	2.68	3	9	34	45	3.08	<1	0.28	11	0.71	1577	3	0.01	2	1029	105	0.90	<5	3	78	<5	<0.01	<10	<10	36	<10	257	3
121575	166.4	0.78	235	231	<0.5	77	5.43	7	18	23	3661	3.51	5	0.16	<10	0.20	682	78	0.03	36	666	227	1.36	263	2	177	<5	0.08	<10	<10	22	30	259	10
121576	<0.2	0.56	37	190	<0.5	<5	2.46	1	9	41	17	3.29	<1	0.33	10	0.83	1660	<2	0.01	2	1014	81	0.69	<5	3	80	<5	<0.01	<10	<10	36	<10	119	3
121577	<0.2	0.64	44	69	<0.5	<5	1.32	1	5	20	9	1.90	<1	0.13	<10	0.44	770	<2	0.01	1	576	2	0.40	<5	2	33	<5	<0.01	<10	<10	25	<10	46	2
121578	<0.2	1.31	70	98	<0.5	<5	2.52	2	9	42	10	3.78	<1	0.25	12	0.93	1424	2	0.02	2	1144	7	0.77	<5	4	61	<5	<0.01	<10	<10	52	<10	86	3
121579	<0.2	1.31	44	106	<0.5	<5	3.25	1	9	43	4	3.50	<1	0.28	10	0.89	1460	2	0.02	2	1041	7	0.69	<5	3	90	<5	<0.01	<10	<10	46	<10	81	3
121580	<0.2	1.00	35	85	<0.5	<5	3.18	1	7	44	9	2.66	<1	0.33	11	0.60	1415	2	0.01	1	782	6	0.64	<5	2	87	<5	<0.01	<10	<10	28	<10	57	3
121581	<0.2	1.12	78	80	<0.5	<5	2.91	2	8	32	6	3.17	<1	0.25	12	0.73	1312	3	0.02	1	944	6	1.01	<5	2	71	<5	<0.01	<10	<10	37	<10	64	4
121582	<0.2	1.18	81	98	<0.5	<5	3.02	3	9	35	8	3.43	<1	0.30	10	0.77	1548	3	0.01	1	1037	20	1.08	<5	3	81	<5	0.01	<10	<10	45	<10	526	3
121583	1.4	1.32	77	124	<0.5	<5	3.59	6	12	30	30	4.01	<1	0.33	10	0.77	1711	2	0.02	1	1151	828	1.57	<5	4	99	<5	0.05	<10	<10	59	18	1165	5
121584	<0.2	1.28	64	89	<0.5	<5	3.31	2	9	31	15	3.42	<1	0.31	<10	0.81	1855	2	0.02	1	1010	38	0.92	<5	3	83	<5	0.01	<10	<10	49	<10	99	4
121585	<0.2	1.19	96	103	<0.5	<5	3.58	3	11	27	23	3.57	<1	0.28	11	0.72	1744	4	0.02	2	1140	180	1.19	<5	4	70	<5	0.03	<10	<10	50	<10	274	4
121586	<0.2	0.97	98	103	<0.5	<5	3.09	2	10	32	10	3.50	<1	0.29	12	0.73	1619	3	0.02	1	1098	17	1.06	<5	3	72	<5	0.01	<10	<10	41	<10	107	3
121587	0.2	1.01	70	134	<0.5	<5	4.65	2	9	24	13	3.30	1	0.29	<10	0.87	2155	2	0.01	2	1038	43	0.99	<5	3	142	<5	<0.01	<10	13	40	<10	103	2
121588	0.2	1.24	150	91	<0.5	<5	4.10	4	9	25	12	3.40	1	0.29	11	0.88	1943	2	0.01	2	1146	41	0.89	<5	3	130	<5	<0.01	<10	<10	46	<10	95	3
121589	<0.2	1.46	85	88	<0.5	<5	3.22	2	10	26	12	3.77	1	0.31	12	0.88	1649	2	0.01	1	1220	45	1.02	<5	3	102	<5	0.01	<10	<10	51	<10	136	4
121590	<0.2	1.38	55	143	<0.5	<5	2.88	1	10	33	5	3.50	1	0.29	12	0.84	1404	2	0.02	1	1166	14	0.94	<5	4	70	<5	0.02	<10	<10	52	<10	88	4
121591	<0.2	1.21	66	92	<0.5	<5	2.40	2	9	27	4	3.39	1	0.25	10	0.76	1312	2	0.02	1	1044	15	1.03	<5	3	54	<5	<0.01	<10	<10	43	<10	110	3
121592	<0.2	1.06	57	76	<0.5	<5	4.80	1	8	32	2	3.04	<1	0.30	10	0.69	1792	2	0.01	1	932	13	1.01	<5	3	94	<5	<0.01	<10	<10	39	<10	89	2
121593	0.3	0.82	71	91	<0.5	<5	4.06	2	7	30	3	3.02	<1	0.29	<10	0.60	1553	<2	0.02	2	867	13	1.15	<5	2	84	<5	<0.01	<10	<10	31	<10	68	2
121594	<0.2	0.52	57	226	<0.5	<5	5.24	1	6	37	5	2.47	<1	0.31	<10	0.47	1601	2	0.01	1	687	10	0.78	<5	2	134	<5	<0.01	<10	<10	15	<10	41	2
121595	<0.2	0.36	32	119	<0.5	<5	5.52	1	7	32	6	2.25	<1	0.34	<10	0.58	1852	2	0.01	2	681	10	0.74	<5	2	340	<5	<0.01	<10	<10	7	<10	29	2
121596	2.1	3.73	65	78	<0.5	8	7.42	1	39	291	210	7.00	1	0.10	<10	4.88	2507	9	0.01	43	1806	60	0.68	<5	25	220	<5	<0.01	<10	12	212	<10	113	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3498RJ

Date : Oct-10-08

Ascot Resources Ltd

Attention: Sue Dean

Project: Dilworth/shipment 30

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121597	1.0	2.60	89	83	<0.5	7	8.94	2	33	235	136	6.21	1	0.14	<10	3.53	2464	5	0.01	39	1788	21	0.83	<5	21	365	<5	<0.01	<10	17	164	<10	91	2
121598	0.9	2.79	66	111	<0.5	7	8.68	1	32	260	130	5.63	1	0.13	<10	3.28	2174	<2	0.01	39	1809	15	0.69	<5	21	208	<5	<0.01	<10	12	183	<10	71	2
121599	1.5	2.20	90	73	<0.5	7	9.08	2	36	253	108	5.35	1	0.14	<10	2.65	2357	<2	0.01	42	1795	12	0.62	<5	24	250	<5	<0.01	<10	13	182	<10	77	2
121600	<0.2	1.16	<5	258	<0.5	<5	1.09	<1	10	113	3	2.35	1	0.52	<10	0.82	721	<2	0.07	8	844	5	0.03	<5	4	60	<5	0.14	<10	<10	52	<10	55	2
121601	1.4	2.23	109	54	<0.5	<5	9.60	2	33	277	86	5.07	1	0.10	<10	2.09	2761	<2	0.01	37	1774	15	0.92	<5	22	215	<5	0.06	<10	12	213	<10	114	3
121602	1.7	1.80	77	66	<0.5	<5	11.13	2	35	287	89	4.23	1	0.10	<10	1.85	2641	<2	0.01	38	1780	15	1.13	<5	23	180	<5	0.12	<10	<10	210	<10	74	3
121603	1.6	1.82	75	75	<0.5	<5	6.06	1	33	231	93	4.32	1	0.13	<10	1.95	1579	<2	0.01	33	1790	13	0.94	<5	10	104	<5	0.13	<10	<10	157	<10	57	4
121604	2.0	2.12	71	62	<0.5	<5	8.59	2	35	280	99	5.10	1	0.10	<10	2.01	2315	<2	0.01	39	1861	10	1.02	<5	19	153	<5	0.13	<10	<10	207	<10	72	4
121605	3.0	1.83	87	64	<0.5	<5	9.51	2	38	311	147	4.74	1	0.10	<10	1.67	2805	<2	0.01	41	1988	12	1.36	<5	27	168	<5	0.12	<10	<10	236	<10	58	4
121606	0.6	1.59	44	92	<0.5	7	>15.00	1	19	179	47	3.60	<1	0.09	<10	1.33	3766	<2	0.01	26	1102	14	0.45	<5	16	288	<5	0.01	<10	18	127	<10	42	1
121607	1.4	2.12	91	64	<0.5	5	12.59	2	36	240	115	5.19	1	0.12	<10	1.87	2339	<2	0.01	38	1587	11	1.31	<5	21	242	<5	0.05	<10	13	176	<10	46	4
121608	<0.2	1.25	47	112	<0.5	<5	7.77	1	9	32	19	2.97	<1	0.27	<10	0.75	1742	<2	0.02	2	1056	13	0.49	<5	3	599	<5	<0.01	<10	<10	34	<10	75	1
121609	0.2	2.15	49	150	<0.5	<5	3.44	1	15	9	28	5.40	<1	0.29	<10	1.54	1999	<2	0.02	3	1612	15	0.93	<5	3	96	<5	<0.01	<10	15	59	<10	127	2
121610	0.3	1.67	47	129	<0.5	<5	2.03	1	16	9	39	4.94	<1	0.33	<10	1.09	1568	<2	0.02	2	1702	9	1.29	<5	2	61	<5	<0.01	<10	<10	47	<10	100	2
121611	0.2	1.40	60	162	<0.5	<5	3.19	2	15	7	25	4.98	<1	0.33	<10	0.88	2083	<2	0.02	2	1676	34	0.61	<5	3	93	<5	<0.01	<10	10	37	<10	207	2
121612	<0.2	1.37	12	117	<0.5	<5	3.48	<1	13	37	9	3.67	<1	0.26	18	1.31	765	<2	0.03	12	1646	11	0.25	<5	3	209	<5	<0.01	<10	<10	37	<10	105	3
121613	<0.2	1.38	5	163	<0.5	<5	3.17	<1	13	43	2	3.48	<1	0.20	19	1.43	827	<2	0.04	14	1700	<2	0.20	<5	4	185	<5	0.01	<10	<10	49	<10	80	3
121614	0.4	1.63	55	112	0.7	<5	4.27	1	22	27	51	4.84	<1	0.40	<10	0.86	1849	<2	0.01	7	1704	30	1.30	<5	5	226	<5	<0.01	<10	<10	47	<10	104	2
121615	<0.2	1.57	5	444	<0.5	<5	3.39	<1	14	46	3	3.53	<1	0.21	24	1.47	728	<2	0.04	14	1701	2	0.11	<5	4	175	<5	0.01	<10	<10	58	<10	74	4
121616	1.1	2.25	241	122	<0.5	<5	3.79	6	21	54	48	6.12	<1	0.31	<10	1.36	2082	<2	0.01	11	1842	23	1.48	<5	6	117	<5	0.01	<10	14	83	<10	92	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3551-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 31**
Attn: **Sue Deane**

Oct-16-08

We hereby certify the following assay of 22 core samples submitted Oct-03-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121617	0.02	0.03	1.2
121618	<0.01		0.2
121619	0.01		0.9
121620	0.02		0.4
121621	0.03		0.4
121622	0.04		0.4
121623	0.02		<0.1
121624	0.02		<0.1
121625	0.47		0.2
121626	0.01	<0.01	<0.1
121627	0.01		<0.1
121628	0.43		0.7
121629	0.02		0.9
121630	0.02		0.4
121631	0.01		<0.1
121632	0.01		<0.1
121633	0.02		<0.1
121634	0.01		<0.1
121635	0.03		0.3
121636	0.01	0.01	0.4
121637	0.03		0.5
121638	0.06		0.9
*0211	2.26		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3551-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 31**
Attn: **Sue Deane**

Oct-16-08

We hereby certify the following assay of 22 core samples submitted Oct-03-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121639	0.03	0.02	1.1
121640	0.31		1.1
121641	0.05		1.6
121642	0.19		1.5
121643	0.06		1.8
121644	0.01		0.8
121645	0.03		1.3
121646	0.03		1.2
121647	0.05		1.3
121648	0.08	0.10	1.1
121649	0.02		1.1
121650	0.01		<0.1
121651	0.03		1.6
121652	0.16		2.9
121653	0.14		5.7
121654	0.11		3.2
121655	0.08		2.1
121656	0.26		2.4
121657	0.13		3.1
121658	0.11	0.10	2.6
121659	0.11		2.3
121660	0.01		<0.1
*0211	2.18		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3551-RA3

Company: **Ascot Resources Ltd**
 Project: **Dilworth/Shipment 31**
 Attn: **Sue Deane**

Oct-16-08

We hereby certify the following assay of 22 core samples submitted Oct-03-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
121661	0.05	0.05	0.6	
121662	0.07		0.8	
121663	0.03		0.2	
121664	0.01		<0.1	
121665	0.05		2.7	
121666	0.13		2.8	
121667	0.26		1.1	
121668	0.02		<0.1	
121669	0.01		<0.1	
121670	0.01	0.01	<0.1	
121671	0.28		0.7	
121672	0.01		<0.1	
121673	0.04		1.4	
121674	0.08		0.7	
121675	0.14		>200	287.7
121676	0.08		2.5	
121677	0.05		1.1	
121678	0.08		0.6	
121679	0.05		1.1	
121680	0.03	0.02	1.1	
121681	0.74		1.9	
121682	0.04		1.0	
*0211	2.23			
*CCu-1c				131.6
*BLANK	<0.01			<0.1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3551-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 31**
Attn: **Sue Deane**

Oct-16-08

We hereby certify the following assay of 22 core samples submitted Oct-03-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121683	0.03	0.02	1.3
121684	0.06		1.2
121685	0.01		<0.1
121686	0.01		<0.1
121687	0.04		0.4
121688	0.02		0.2
121689	0.02		0.3
121690	0.02		0.1
121691	0.02		<0.1
121692	0.02	0.02	<0.1
121693	0.01		0.1
121694	0.01		<0.1
121695	0.02		0.2
121696	0.02		0.3
121697	0.03		0.5
121698	0.02		0.7
121699	0.02		0.4
121700	0.01		<0.1
121701	0.03		0.6
121702	0.03	0.03	1.0
121703	0.04		0.3
121704	0.05		1.1
*0211	2.21		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3551-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 31**
Attn: **Sue Deane**

Oct-16-08

We hereby certify the following assay of 22 core samples submitted Oct-03-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121705	0.05	0.05	0.9
121706	0.04		2.1
121707	0.98		3.3
121708	0.82		5.0
121709	0.03		0.9
121710	0.05		1.3
121711	0.02		2.8
121712	0.40		0.9
121713	0.08		0.2
121714	0.05	0.04	0.4
121715	0.04		1.0
121716	0.03		1.3
121717	0.04		1.9
130292	0.62		5.6
130293	0.52		4.1
130294	0.19		2.7
130295	0.12		3.2
130296	0.21		2.9
130297	0.20		4.6
130298	0.15	0.15	5.3
130299	0.19		6.4
130300	0.01		<0.1
*0211	2.15		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3551-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 31**
Attn: **Sue Deane**

Oct-16-08

We hereby certify the following assay of 22 core samples submitted Oct-03-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130301	0.20	0.20	4.3
130302	0.12		2.8
130303	0.04		0.8
130304	0.05		1.3
130305	0.02		0.9
130306	0.03		1.7
130307	0.05		2.0
130308	0.08		2.3
130309	0.16		1.8
130310	0.17	0.17	1.0
130311	0.16		2.1
130312	0.09		1.5
130313	0.04		1.5
130314	0.03		1.4
130315	0.01		0.8
130316	0.03		0.8
130317	0.07		1.3
130318	0.05		1.6
130319	0.03		1.4
130320	0.04	0.03	1.6
130321	0.06		1.9
130322	0.03		1.4
*0211	2.17		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3551-RA7

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 31**
Attn: **Sue Deane**

Oct-16-08

We hereby certify the following assay of 22 core samples submitted Oct-03-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130323	0.02	0.02	1.3
130324	0.03		1.3
130325	6.86		3.0
130326	0.04		1.4
130327	0.04		1.5
130328	0.02		1.3
130329	0.04		1.5
130330	0.08		2.2
130331	0.03		1.4
130332	0.02	0.02	1.5
130333	0.07		1.8
130334	0.04		1.6
130335	0.02		1.1
130336	0.02		1.2
130337	0.15		1.1
130338	0.02		1.3
130339	0.04		1.6
130340	0.04		1.7
130341	0.11		1.3
130342	0.01	0.01	0.3
130343	0.02		0.5
130344	0.01		0.2
*0211	2.30		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3551-RA8

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 31**
Attn: **Sue Deane**

Oct-16-08

We hereby certify the following assay of 22 core samples submitted Oct-03-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130345	0.01	0.01	0.6
130346	0.01		0.6
130347	0.03		1.0
130348	0.07		1.6
130349	0.08		1.8
130350	<0.01		2.4
130351	0.24		2.2
130352	0.23		1.4
130353	0.18		1.7
130354	0.11	0.13	1.4
130355	0.15		1.4
130356	0.51		1.1
130357	0.24		1.4
130358	0.25		1.0
130359	0.39		1.8
130360	1.05		4.8
130361	0.71		9.0
130362	0.57		12.8
130363	0.34		8.5
130364	1.44	1.48	12.2
130365	1.86		24.8
130366	0.16		2.9
*0211	2.20		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3551-RA9

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 31**
Attn: **Sue Deane**

Oct-16-08

We hereby certify the following assay of 22 core samples submitted Oct-03-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130367	0.06	0.06	1.7
130368	0.04		2.5
130369	0.03		2.2
130370	0.04		2.2
130371	0.06		2.1
130372	0.05		1.4
130373	0.18		1.3
130374	0.22		3.4
130375	0.43		0.1
130376	0.02	0.02	2.1
130377	0.04		1.9
130378	0.07		1.1
130379	0.01		0.7
130380	<0.01		0.2
130381	0.02		<0.1
130382	0.03		2.2
130383	0.04		0.5
130384	0.05		1.5
130385	0.05		2.2
130386	0.06	0.04	1.7
130387	0.04		1.8
130388	0.04		1.8
*0211	2.21		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3551-RA10

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 31**
Attn: **Sue Deane**

Oct-16-08

We hereby certify the following assay of 22 core samples submitted Oct-03-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130389	0.09	0.05	2.0
130390	0.06		2.2
130391	0.05		1.3
130392	0.15		2.6
130393	0.08		0.8
130394	0.07		1.3
130395	0.20		2.4
130396	0.02		0.5
130397	0.09		0.7
130398	0.10	0.11	0.4
130399	0.13		0.3
130400	<0.01		<0.1
130401	0.15		1.0
130402	0.04		1.2
130403	0.15		1.3
130404	0.05		0.9
130405	0.01		1.3
130406	0.04		1.8
130407	0.01		2.0
130408	0.10	0.07	2.6
130409	0.22		1.6
130410	0.06		1.7
*0211	2.21		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3551-RA11

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 31**
Attn: **Sue Deane**

Oct-16-08

We *hereby certify* the following assay of 14 core samples submitted Oct-03-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130411	0.04	0.04	1.3
130412	0.35		0.7
130413	0.27		1.2
130414	0.07		1.8
130415	0.11		1.5
130416	0.03		0.9
130417	0.03		1.1
130418	0.03		0.8
130419	0.04		0.9
130420	0.12	0.11	1.3
130421	0.02		1.2
130422	0.16		1.4
130423	0.23		1.1
*0211	2.19		
*BLANK	<0.01		

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3551RJ

Date : Oct-16-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 31

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121617	1.2	1.43	81	249	<0.5	<5	2.61	2	16	38	53	3.82	<1	0.54	<10	0.52	1172	<2	0.01	7	1666	17	1.53	<5	4	101	<5	<0.01	<10	<10	43	<10	58	2
121618	0.2	1.38	46	163	<0.5	<5	3.14	1	23	29	51	3.82	<1	0.46	<10	0.61	1459	<2	0.02	6	1541	12	0.54	<5	3	117	<5	<0.01	<10	<10	37	<10	74	2
121619	0.9	1.58	77	130	<0.5	6	2.52	2	40	6	85	6.25	<1	0.46	<10	1.01	1698	<2	0.02	9	1466	23	1.72	<5	4	107	<5	<0.01	<10	12	61	<10	120	3
121620	0.4	0.76	46	314	0.6	6	5.28	1	18	4	34	4.82	<1	0.56	<10	0.72	2065	<2	0.01	3	1464	21	1.21	<5	3	231	<5	<0.01	<10	16	29	<10	107	2
121621	0.4	0.98	45	489	0.6	6	2.82	1	19	11	33	4.80	<1	0.54	<10	0.54	1577	<2	0.01	5	1682	22	0.53	<5	4	131	<5	<0.01	<10	<10	32	<10	113	2
121622	0.4	1.01	53	207	0.6	5	0.63	2	22	40	32	4.76	<1	0.43	10	0.28	1284	<2	0.01	9	1884	21	0.18	<5	5	22	<5	<0.01	<10	<10	35	<10	140	2
121623	<0.2	1.11	5	94	<0.5	<5	2.63	<1	8	27	1	2.05	<1	0.36	16	0.65	449	<2	0.04	4	960	11	0.22	<5	2	154	<5	<0.01	<10	<10	20	<10	51	6
121624	<0.2	1.28	<5	96	<0.5	<5	3.02	<1	8	22	3	2.10	<1	0.40	17	0.69	484	<2	0.05	4	980	12	0.22	<5	2	185	<5	<0.01	<10	<10	21	<10	51	6
121625	0.2	1.07	7116	24	<0.5	20	6.31	188	181	14	73	3.67	<1	0.05	12	0.24	776	16	0.09	33	1429	13	1.47	<5	2	100	<5	0.07	<10	<10	41	<10	97	12
121626	<0.2	1.95	<5	554	<0.5	<5	3.01	<1	16	56	17	4.02	<1	0.16	28	1.48	720	<2	0.04	13	2062	7	0.07	<5	5	132	<5	0.01	<10	<10	51	<10	109	4
121627	<0.2	1.91	<5	726	<0.5	<5	2.79	<1	21	53	7	3.96	<1	0.15	27	1.51	724	<2	0.05	12	1979	6	0.03	<5	6	80	<5	0.28	<10	<10	72	<10	105	13
121628	0.7	2.03	51	65	<0.5	<5	8.47	1	22	75	134	4.37	<1	0.18	<10	1.13	1693	<2	0.05	13	1126	6	0.58	<5	9	199	<5	0.10	<10	<10	120	<10	78	6
121629	0.9	3.51	45	104	<0.5	<5	4.01	1	39	155	120	7.31	<1	0.21	<10	2.61	1673	<2	0.03	32	1886	14	0.61	<5	23	153	<5	0.17	<10	<10	235	<10	119	6
121630	0.4	3.74	31	117	<0.5	<5	6.38	<1	39	162	106	6.64	1	0.23	<10	3.29	2007	<2	0.03	28	1777	10	0.33	<5	25	216	<5	0.15	<10	11	243	<10	94	6
121631	<0.2	0.44	9	45	<0.5	<5	1.65	<1	7	54	20	1.49	<1	0.22	11	0.42	575	2	0.05	5	241	25	0.10	<5	3	101	10	<0.01	<10	<10	23	<10	32	9
121632	<0.2	0.26	<5	25	<0.5	<5	0.54	<1	1	53	1	0.46	<1	0.22	13	0.04	281	<2	0.06	2	28	23	0.03	<5	1	16	13	<0.01	<10	<10	2	<10	14	7
121633	<0.2	1.51	<5	164	0.8	5	2.80	<1	18	69	15	4.46	<1	0.26	28	1.68	834	<2	0.04	16	2464	12	0.15	<5	6	175	<5	<0.01	<10	<10	54	<10	127	4
121634	<0.2	0.26	<5	34	<0.5	<5	0.32	<1	1	88	2	0.47	<1	0.22	11	0.08	155	<2	0.05	3	77	14	0.04	<5	<1	23	11	<0.01	<10	<10	2	<10	8	6
121635	0.3	3.30	22	262	<0.5	7	6.55	1	32	136	93	6.34	1	0.45	<10	3.06	2009	<2	0.04	24	1750	30	0.43	<5	21	249	<5	0.05	<10	12	205	<10	141	4
121636	0.4	3.03	31	66	<0.5	7	6.17	<1	32	137	65	5.97	<1	0.20	<10	2.67	1637	<2	0.01	26	1675	20	0.57	<5	17	171	<5	0.01	<10	<10	186	<10	78	3
121637	0.5	3.07	34	77	<0.5	8	4.76	<1	35	135	84	6.39	<1	0.24	<10	2.46	1555	<2	0.01	29	1796	24	0.70	<5	15	151	<5	0.01	<10	<10	177	<10	90	3
121638	0.9	3.24	38	49	<0.5	8	4.28	1	33	129	103	6.71	<1	0.18	<10	2.79	1586	<2	0.01	27	1661	22	0.77	<5	15	189	<5	0.01	<10	13	167	<10	109	3
121639	1.1	3.78	38	40	<0.5	7	7.87	<1	29	126	83	7.03	<1	0.19	<10	3.71	2157	<2	0.01	24	1684	20	0.71	<5	14	247	<5	0.02	<10	17	174	<10	80	4
121640	1.1	3.00	1343	55	<0.5	7	7.73	32	34	129	70	6.37	<1	0.31	<10	2.49	2096	<2	0.01	26	1815	32	1.39	<5	12	244	<5	0.01	<10	16	145	<10	82	3
121641	1.6	3.13	192	61	<0.5	<5	8.31	4	42	142	86	6.28	<1	0.29	<10	2.60	2022	<2	0.01	31	1839	19	0.83	<5	15	274	<5	0.05	<10	14	160	<10	80	4
121642	1.5	3.01	1143	85	<0.5	5	8.30	27	37	116	57	6.00	<1	0.30	<10	2.43	2069	<2	0.01	27	1701	17	0.85	<5	12	235	<5	0.04	<10	15	142	<10	76	3
121643	1.8	3.15	446	58	<0.5	<5	7.94	10	32	121	85	6.35	1	0.26	<10	2.56	2075	<2	0.01	24	1719	15	0.76	<5	15	250	<5	0.06	<10	14	168	<10	86	3
121644	0.8	3.49	84	108	<0.5	6	7.36	2	32	135	61	6.45	1	0.21	<10	3.24	1847	<2	0.01	26	1649	15	0.42	<5	16	238	<5	0.02	<10	13	190	<10	105	3
121645	1.3	3.45	71	662	<0.5	6	5.49	1	36	108	96	6.60	1	0.25	<10	3.01	1819	<2	0.01	26	1807	30	0.58	<5	13	186	<5	0.01	<10	13	162	<10	136	3
121646	1.2	3.20	166	65	<0.5	7	7.70	3	35	125	89	6.46	1	0.22	<10	2.87	2454	<2	0.01	26	1795	22	0.61	<5	14	192	<5	0.01	<10	14	173	<10	112	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3551RJ**

Date : Oct-16-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 31

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121647	1.3	1.79	41	110	<0.5	<5	4.97	2	16	29	97	4.34	<1	0.39	<10	1.08	1688	2	0.01	7	1453	31	0.64	<5	4	133	<5	<0.01	<10	<10	55	<10	104	2
121648	1.1	1.86	152	83	<0.5	<5	7.91	5	16	32	78	3.82	<1	0.37	<10	1.14	1981	<2	0.01	7	1288	19	0.29	<5	5	215	<5	0.01	<10	11	60	<10	103	2
121649	1.1	2.13	43	95	<0.5	<5	8.16	4	20	29	65	4.37	<1	0.40	10	1.22	2036	2	0.01	8	1495	32	0.45	<5	6	215	<5	0.04	<10	12	67	<10	151	2
121650	<0.2	0.12	<5	11	<0.5	10	>15.00	<1	1	4	1	0.16	1	0.05	<10	1.99	142	<2	0.01	1	114	<2	0.03	<5	<1	5426	<5	<0.01	<10	<10	5	<10	1	<1
121651	1.6	2.74	51	102	<0.5	<5	3.84	2	25	44	76	5.99	<1	0.41	<10	1.75	1952	2	0.01	12	1759	41	1.12	<5	6	123	<5	0.03	<10	14	96	<10	157	3
121652	2.9	2.31	195	106	<0.5	<5	5.42	5	22	29	126	5.10	<1	0.45	<10	1.31	2186	5	0.01	9	1668	33	1.10	<5	5	157	<5	0.03	<10	14	74	<10	121	2
121653	5.7	2.01	425	116	<0.5	<5	6.07	10	17	19	169	4.99	<1	0.47	<10	0.93	2161	10	0.01	3	1541	45	1.58	<5	3	188	<5	0.03	<10	16	51	<10	128	2
121654	3.2	2.02	331	122	<0.5	<5	6.74	9	18	9	85	5.04	<1	0.50	<10	0.92	2320	10	0.01	4	1579	51	1.67	<5	3	209	<5	0.03	<10	16	46	<10	158	2
121655	2.1	1.99	62	96	<0.5	<5	7.89	2	10	22	48	4.15	<1	0.39	10	1.07	2463	12	0.01	3	1355	22	0.48	<5	3	201	<5	0.03	<10	15	41	<10	126	2
121656	2.4	1.73	578	91	<0.5	<5	8.60	14	13	14	92	4.66	<1	0.39	10	0.80	2476	2	0.01	3	1080	34	1.67	<5	3	179	<5	0.03	<10	16	46	<10	121	2
121657	3.1	2.59	157	103	<0.5	<5	6.06	5	21	10	294	6.66	<1	0.36	10	1.41	2681	<2	0.02	4	1455	27	1.57	<5	4	169	<5	0.08	<10	21	83	<10	183	3
121658	2.6	1.54	46	114	<0.5	<5	7.35	5	14	10	229	3.53	<1	0.38	10	0.64	1911	5	0.02	2	1287	57	0.57	<5	3	187	<5	0.05	<10	10	39	<10	348	5
121659	2.3	2.11	35	144	<0.5	<5	4.27	4	19	9	258	5.45	<1	0.47	13	1.03	2024	<2	0.02	3	1577	26	0.81	<5	4	120	<5	0.02	<10	13	63	<10	416	3
121660	<0.2	0.99	36	83	<0.5	<5	3.17	1	18	37	18	4.72	<1	0.19	17	1.01	1549	<2	0.03	14	2434	14	0.13	<5	4	203	<5	<0.01	<10	<10	48	<10	136	4
121661	0.6	1.89	52	151	<0.5	<5	4.61	2	14	24	42	4.47	<1	0.46	16	0.86	1761	<2	0.01	3	1587	40	1.07	<5	3	135	<5	0.01	<10	<10	39	<10	202	2
121662	0.8	1.83	43	145	<0.5	<5	5.10	2	13	11	71	4.22	<1	0.44	13	0.81	1767	<2	0.02	2	1415	29	0.90	<5	2	145	<5	0.01	<10	11	36	<10	145	2
121663	0.2	1.78	30	143	<0.5	<5	4.08	1	12	12	36	4.06	<1	0.44	13	0.84	1724	<2	0.02	2	1406	17	0.69	<5	2	115	<5	0.01	<10	<10	43	<10	117	2
121664	<0.2	0.38	<5	37	<0.5	<5	0.71	<1	1	67	<1	0.62	<1	0.21	13	0.03	374	2	0.06	2	32	24	0.04	<5	<1	21	9	<0.01	<10	<10	1	<10	21	5
121665	2.7	2.27	53	142	<0.5	5	5.04	3	22	7	185	5.68	<1	0.43	12	1.07	2078	5	0.02	4	1846	63	1.30	<5	4	139	<5	0.04	<10	13	72	<10	327	3
121666	2.8	2.19	144	147	<0.5	<5	5.43	4	23	9	149	5.76	<1	0.45	<10	1.00	2070	<2	0.02	4	1622	64	1.93	<5	4	202	<5	0.09	<10	17	59	<10	177	3
121667	1.1	1.78	303	139	<0.5	<5	5.11	8	13	11	54	3.78	<1	0.46	10	0.80	1767	<2	0.01	2	1389	45	0.76	<5	3	140	<5	0.07	<10	<10	35	<10	92	2
121668	<0.2	2.33	19	178	<0.5	<5	4.90	1	13	12	19	4.04	<1	0.45	<10	0.90	1652	<2	0.10	1	1403	17	0.53	<5	4	138	<5	0.16	<10	10	54	<10	155	3
121669	<0.2	1.91	<5	356	<0.5	<5	2.38	<1	23	64	7	4.25	<1	0.15	22	1.48	750	<2	0.05	12	2049	9	0.05	<5	7	50	<5	0.42	<10	<10	81	<10	116	19
121670	<0.2	1.83	<5	81	<0.5	<5	2.51	<1	23	60	10	4.01	<1	0.11	22	1.41	705	<2	0.05	12	2025	8	0.07	<5	6	60	<5	0.43	<10	<10	73	<10	112	28
121671	0.7	3.76	45	164	<0.5	<5	6.02	2	21	16	68	5.02	<1	0.46	<10	1.30	1917	2	0.18	4	1647	35	0.61	<5	6	197	<5	0.19	<10	12	94	<10	180	5
121672	<0.2	2.10	9	84	<0.5	<5	2.42	<1	28	68	16	4.55	<1	0.11	25	1.72	794	<2	0.10	16	2792	14	0.18	<5	5	79	<5	0.48	<10	<10	87	<10	130	37
121673	1.4	3.26	51	176	<0.5	<5	6.69	2	22	7	103	5.43	<1	0.47	<10	1.54	2554	<2	0.09	3	1490	25	0.71	<5	5	192	<5	0.17	<10	17	83	<10	138	3
121674	0.7	1.35	469	118	<0.5	<5	5.52	12	12	13	40	3.75	<1	0.49	<10	0.51	1803	<2	0.01	2	1308	43	1.91	<5	2	146	<5	0.09	<10	<10	27	<10	88	2
121675	>200.0	0.67	627	199	<0.5	118	0.58	25	8	20	8042	2.37	7	0.17	<10	0.61	301	600	0.03	5	455	961	1.24	1796	2	74	<5	0.06	<10	<10	20	<10	987	2
121676	2.5	0.93	543	85	<0.5	<5	12.37	18	10	21	54	2.73	<1	0.35	<10	0.34	3075	2	0.01	2	784	119	1.57	5	2	312	<5	0.04	<10	17	22	<10	506	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3551RJ**

Date : Oct-16-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 31

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121677	1.1	2.12	109	116	<0.5	<5	5.36	3	19	9	42	5.08	<1	0.45	<10	0.94	2065	7	0.01	3	1342	50	1.14	<5	3	149	<5	0.11	<10	15	46	<10	129	2
121678	0.6	2.44	87	144	<0.5	<5	6.01	2	20	8	23	5.36	<1	0.51	<10	1.11	2227	5	0.01	3	1541	32	0.89	<5	3	198	<5	0.15	<10	15	55	<10	98	3
121679	1.1	2.15	107	123	<0.5	<5	4.80	2	20	24	40	4.91	<1	0.45	<10	1.04	1831	<2	0.01	4	1390	39	1.15	<5	3	142	<5	0.12	<10	15	45	<10	78	2
121680	1.1	2.59	46	132	<0.5	<5	4.47	1	24	8	34	5.79	<1	0.46	<10	1.37	2159	<2	0.01	4	1585	35	1.13	<5	4	124	<5	0.14	<10	15	65	<10	106	3
121681	1.9	2.31	392	132	<0.5	<5	4.36	10	22	7	40	5.60	<1	0.47	<10	1.16	2187	4	0.01	4	1610	85	1.67	<5	3	147	<5	0.08	<10	17	60	<10	154	2
121682	1.0	2.42	63	137	<0.5	<5	5.13	3	26	13	94	6.13	<1	0.48	<10	1.00	1891	4	0.02	6	1655	33	1.50	<5	6	148	<5	0.09	<10	13	96	<10	127	4
121683	1.3	3.75	50	105	<0.5	<5	6.12	1	44	9	129	9.28	<1	0.33	<10	1.96	2755	5	0.02	9	1743	40	1.32	<5	8	173	<5	0.15	<10	23	157	<10	133	6
121684	1.2	3.03	49	136	<0.5	<5	6.48	2	30	8	82	7.16	<1	0.44	<10	1.41	2323	5	0.02	7	1748	31	0.91	<5	6	164	<5	0.14	<10	18	90	<10	136	5
121685	<0.2	0.36	<5	31	<0.5	5	>15.00	<1	2	119	<1	0.80	<1	0.11	<10	0.14	1791	2	0.01	3	93	4	0.04	<5	1	1041	<5	0.01	<10	<10	8	<10	12	<1
121686	<0.2	0.75	11	64	<0.5	<5	>15.00	1	6	49	<1	1.62	<1	0.21	<10	0.30	2277	<2	0.01	2	306	32	0.17	<5	2	1257	<5	0.04	<10	14	16	<10	39	1
121687	0.4	2.62	41	155	<0.5	<5	4.23	2	25	8	37	6.02	<1	0.49	<10	1.29	1826	<2	0.02	4	1853	46	0.86	<5	4	96	<5	0.13	<10	15	62	<10	130	4
121688	0.2	2.81	24	131	<0.5	<5	5.73	1	22	5	29	5.83	<1	0.39	<10	1.83	2142	<2	0.03	4	1733	45	0.67	<5	5	154	<5	0.14	<10	15	80	<10	121	4
121689	0.3	2.67	32	164	<0.5	<5	6.06	2	24	5	39	5.99	<1	0.47	<10	1.43	2064	<2	0.03	4	1676	51	0.86	<5	5	164	<5	0.11	<10	15	78	<10	117	4
121690	<0.2	2.50	26	156	<0.5	<5	5.40	2	20	3	31	5.44	<1	0.46	<10	1.36	1911	<2	0.03	3	1713	41	0.70	<5	5	144	<5	0.12	<10	13	64	<10	118	4
121691	<0.2	2.68	19	154	<0.5	<5	6.76	1	20	4	25	5.62	<1	0.50	<10	1.39	2160	<2	0.03	3	1732	43	0.55	<5	5	189	<5	0.13	<10	15	65	<10	107	4
121692	<0.2	2.50	30	129	<0.5	<5	5.64	1	21	3	24	5.43	<1	0.42	<10	1.40	2040	<2	0.03	3	1708	36	0.82	<5	4	145	<5	0.13	<10	14	61	<10	120	3
121693	<0.2	2.68	35	118	<0.5	<5	5.50	1	20	4	23	5.93	<1	0.40	<10	1.56	2229	<2	0.03	3	1737	35	0.89	<5	4	159	<5	0.10	<10	15	70	<10	122	3
121694	<0.2	2.69	36	130	<0.5	<5	5.01	2	21	16	23	6.00	<1	0.43	12	1.48	2159	<2	0.03	3	1889	37	0.88	<5	4	136	<5	0.10	<10	15	68	<10	157	3
121695	0.2	2.35	67	147	<0.5	<5	5.53	2	21	5	24	5.54	<1	0.48	11	1.25	2027	<2	0.03	3	1751	32	1.47	<5	3	139	<5	0.12	<10	14	74	<10	118	3
121696	0.3	2.39	73	141	<0.5	<5	6.75	2	20	3	19	5.43	<1	0.46	11	1.31	2443	<2	0.03	3	1840	34	1.31	<5	3	176	<5	0.12	<10	14	67	<10	126	3
121697	0.5	2.78	58	133	<0.5	<5	6.52	2	21	4	26	6.01	<1	0.46	10	1.61	2382	<2	0.03	3	1825	36	1.03	<5	4	190	<5	0.11	<10	16	70	<10	95	3
121698	0.7	2.19	96	141	<0.5	<5	4.03	3	18	6	43	4.96	<1	0.47	13	1.07	1813	<2	0.02	3	1698	45	1.09	<5	2	111	<5	0.08	<10	<10	42	<10	84	2
121699	0.4	2.15	101	159	<0.5	<5	7.93	4	19	8	32	4.91	<1	0.53	10	0.96	2377	4	0.02	4	1669	34	1.01	<5	3	229	<5	0.09	<10	10	51	<10	121	2
121700	<0.2	0.10	<5	13	<0.5	10	>15.00	<1	1	1	<1	0.08	<1	0.05	<10	1.62	55	<2	0.01	<1	63	<2	0.12	<5	<1	5854	<5	<0.01	<10	<10	2	<10	2	<1
121701	0.6	1.93	210	137	<0.5	<5	9.28	7	16	6	39	4.40	<1	0.47	10	0.88	2444	<2	0.02	2	1586	36	0.87	<5	2	256	<5	0.04	<10	15	51	<10	106	2
121702	1.0	2.16	148	360	<0.5	6	7.32	13	16	13	32	5.32	<1	0.47	10	1.00	2772	2	0.02	3	1636	133	1.29	<5	2	257	<5	<0.01	<10	19	46	15	874	2
121703	0.3	1.90	134	124	<0.5	<5	7.08	4	12	26	17	4.48	<1	0.45	<10	0.85	2443	2	0.02	4	1485	41	1.04	<5	2	194	<5	<0.01	<10	16	39	<10	135	2
121704	1.1	1.99	638	125	<0.5	6	6.05	16	18	12	37	5.67	<1	0.46	<10	0.90	2372	<2	0.02	4	1785	33	2.21	<5	3	193	<5	<0.01	<10	15	49	<10	156	2
121705	0.9	1.78	523	119	<0.5	5	6.35	13	15	5	37	4.47	<1	0.46	<10	0.72	2244	<2	0.01	3	1514	26	1.45	<5	2	250	<5	<0.01	<10	16	39	<10	108	2
121706	2.1	2.35	361	159	<0.5	6	4.77	9	26	3	86	6.67	<1	0.44	<10	1.15	2273	<2	0.02	5	1666	59	2.41	<5	3	209	<5	<0.01	<10	21	72	<10	145	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3551RJ**

Date : Oct-16-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 31

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121707	3.3	1.74	1555	119	<0.5	7	8.56	38	25	5	64	6.02	<1	0.46	<10	0.78	2661	<2	0.01	5	1429	34	3.81	<5	3	251	<5	<0.01	<10	21	63	<10	131	3
121708	5.0	1.86	1171	119	<0.5	7	7.46	30	20	3	47	5.68	<1	0.42	<10	0.85	2292	<2	0.02	4	1694	101	2.67	<5	3	242	<5	<0.01	<10	18	65	<10	197	2
121709	0.9	2.01	276	139	<0.5	6	7.11	7	24	5	59	5.86	<1	0.44	<10	1.02	2321	<2	0.02	5	1666	15	2.69	<5	4	247	<5	0.01	<10	18	72	<10	106	2
121710	1.3	2.76	387	108	<0.5	9	5.88	9	27	5	53	8.89	<1	0.41	<10	1.51	2755	<2	0.02	6	1747	37	4.39	<5	5	179	<5	0.01	<10	25	98	<10	120	4
121711	2.8	1.64	5795	126	<0.5	7	8.09	143	19	8	39	6.42	<1	0.44	<10	0.76	2911	<2	0.01	4	1258	77	4.02	27	3	315	<5	<0.01	<10	25	48	<10	134	2
121712	0.9	2.32	97	160	<0.5	6	4.44	3	24	4	50	6.01	<1	0.47	<10	1.25	2437	<2	0.02	6	1874	16	2.15	<5	4	148	<5	0.01	<10	13	75	<10	188	3
121713	0.2	2.37	50	227	<0.5	6	3.41	2	22	6	38	6.15	<1	0.43	<10	1.14	2376	<2	0.02	4	1708	26	1.12	<5	4	148	<5	<0.01	<10	18	68	<10	167	3
121714	0.4	2.37	51	189	0.5	6	5.03	3	25	3	27	5.46	<1	0.44	<10	1.44	2714	<2	0.02	5	1673	111	0.83	<5	4	273	<5	<0.01	<10	20	46	<10	284	2
121715	1.0	2.67	111	366	<0.5	6	5.99	3	23	62	47	5.59	<1	0.31	<10	2.13	2623	<2	0.01	14	1559	84	1.08	<5	7	267	<5	<0.01	<10	19	109	<10	176	2
121716	1.3	2.56	243	207	<0.5	6	7.21	6	28	68	67	6.00	1	0.13	<10	2.19	2084	<2	0.02	15	1713	24	1.76	<5	15	230	<5	0.02	<10	13	219	<10	119	3
121717	1.9	2.42	213	87	<0.5	<5	5.89	5	28	47	87	6.01	1	0.17	<10	2.09	1884	<2	0.02	13	1799	31	2.24	<5	12	170	<5	0.06	<10	11	190	<10	161	3
130292	5.6	2.00	823	108	<0.5	7	4.14	19	55	96	117	6.48	<1	0.35	<10	1.88	1847	<2	0.01	42	1967	36	4.74	<5	9	123	<5	<0.01	<10	16	101	<10	81	3
130293	4.1	2.50	1086	121	<0.5	7	5.12	29	38	84	140	6.74	<1	0.32	<10	2.25	2705	<2	0.01	26	1714	186	2.76	<5	9	160	<5	<0.01	<10	20	108	<10	439	3
130294	2.7	1.20	1090	117	<0.5	5	5.42	26	28	39	87	5.16	<1	0.38	<10	0.62	2012	<2	0.01	17	1621	23	4.08	<5	5	126	<5	<0.01	<10	12	46	<10	136	2
130295	3.2	1.35	636	114	<0.5	6	3.65	15	30	38	99	6.15	<1	0.45	<10	0.66	1663	<2	0.01	22	1931	20	>5.00	<5	6	101	<5	<0.01	<10	12	51	<10	87	3
130296	2.9	1.07	2157	114	<0.5	5	4.73	53	26	21	101	5.67	<1	0.45	<10	0.48	2076	<2	0.01	14	1894	22	>5.00	<5	4	140	<5	<0.01	<10	14	38	<10	149	2
130297	4.6	0.94	1136	111	<0.5	<5	2.05	28	32	32	139	4.64	1	0.44	<10	0.40	1057	<2	0.01	21	2216	27	4.28	7	4	63	<5	<0.01	<10	<10	37	<10	219	2
130298	5.3	1.02	546	103	<0.5	<5	3.36	13	29	38	153	5.35	2	0.39	<10	0.53	1307	<2	0.01	21	2120	26	>5.00	13	5	83	<5	<0.01	<10	11	43	<10	51	3
130299	6.4	1.08	859	108	<0.5	5	4.14	21	27	51	101	4.78	1	0.31	<10	0.65	2144	2	0.01	16	1374	55	4.06	20	4	112	<5	<0.01	<10	13	42	<10	184	2
130300	<0.2	1.20	5	306	<0.5	<5	0.63	<1	10	160	<1	2.37	<1	0.66	11	0.71	674	3	0.09	7	863	3	0.04	<5	3	55	<5	0.18	<10	<10	47	<10	56	3
130301	4.3	1.32	336	128	<0.5	5	7.26	8	26	41	74	5.18	<1	0.33	<10	0.83	2708	<2	0.01	15	1262	22	4.15	<5	6	197	<5	<0.01	<10	20	51	<10	123	2
130302	2.8	1.58	593	135	<0.5	<5	5.73	14	31	25	91	5.01	1	0.33	<10	0.93	1892	<2	0.02	16	1777	16	2.87	7	6	160	<5	<0.01	<10	11	53	<10	73	2
130303	0.8	1.44	259	122	<0.5	<5	6.86	6	20	28	66	3.73	<1	0.29	<10	0.99	1706	<2	0.02	11	1512	6	1.80	<5	5	218	<5	<0.01	<10	<10	54	<10	74	2
130304	1.3	1.90	663	136	<0.5	5	7.99	16	22	25	66	4.60	<1	0.32	<10	1.35	2292	<2	0.02	11	1694	9	1.90	<5	5	290	<5	<0.01	<10	16	64	<10	85	2
130305	0.9	1.85	161	136	<0.5	5	8.77	4	23	26	73	4.44	<1	0.30	<10	1.20	2054	<2	0.02	11	1695	7	1.57	<5	6	287	<5	<0.01	<10	14	61	<10	70	2
130306	1.7	1.98	556	149	<0.5	5	7.44	13	24	25	85	5.06	<1	0.32	<10	1.27	2161	<2	0.02	12	1836	13	2.07	<5	6	236	<5	<0.01	<10	16	60	<10	87	2
130307	2.0	2.18	391	133	<0.5	5	6.77	9	26	33	88	5.01	<1	0.29	<10	1.61	2333	<2	0.01	12	1774	10	1.65	<5	6	214	<5	<0.01	<10	18	69	<10	94	2
130308	2.3	2.12	556	126	<0.5	5	5.36	13	26	30	79	5.76	<1	0.29	<10	1.64	2224	<2	0.01	13	1785	15	2.89	<5	6	152	<5	<0.01	<10	17	64	<10	98	2
130309	1.8	0.98	611	118	<0.5	5	6.46	14	24	31	62	5.84	<1	0.31	<10	1.13	2146	<2	0.01	12	1747	22	4.75	<5	6	228	<5	<0.01	<10	15	32	<10	71	2
130310	1.0	0.44	1428	51	<0.5	8	>15.00	34	8	20	28	2.30	<1	0.14	<10	0.57	4534	<2	0.01	3	578	6	1.49	<5	3	861	<5	<0.01	<10	27	16	<10	48	<1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3551RJ**

Date : Oct-16-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 31

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130311	2.1	1.83	1488	126	<0.5	6	7.97	36	22	41	57	5.30	<1	0.28	<10	1.58	2565	3	0.01	10	1648	17	3.41	<5	5	234	<5	<0.01	<10	20	60	<10	81	2
130312	1.5	1.91	202	143	<0.5	6	7.54	4	24	36	59	5.18	<1	0.29	<10	1.62	2281	<2	0.02	11	1712	14	3.12	<5	6	254	<5	<0.01	<10	18	60	<10	73	2
130313	1.5	1.89	131	146	<0.5	6	7.54	3	26	31	77	5.15	<1	0.30	<10	1.48	2262	<2	0.02	12	1795	14	2.92	<5	6	215	<5	<0.01	<10	18	55	<10	88	2
130314	1.4	1.96	188	141	<0.5	6	8.42	5	22	28	85	4.92	<1	0.26	<10	1.56	2866	<2	0.02	10	1676	36	2.47	<5	5	300	<5	<0.01	<10	21	58	<10	140	2
130315	0.8	2.83	188	149	<0.5	5	5.55	4	25	39	72	5.53	<1	0.27	<10	2.33	1820	<2	0.02	12	1909	7	1.12	<5	7	245	<5	<0.01	<10	16	89	<10	81	2
130316	0.8	2.64	136	144	<0.5	6	7.42	3	24	29	71	5.28	<1	0.23	<10	2.37	2116	<2	0.02	12	1682	8	1.74	<5	7	309	<5	<0.01	<10	17	79	<10	74	2
130317	1.3	2.51	243	167	<0.5	7	7.43	5	27	34	83	5.64	1	0.23	<10	2.55	2396	<2	0.02	13	1925	7	1.39	<5	7	271	<5	<0.01	<10	17	78	<10	88	2
130318	1.6	2.23	380	147	<0.5	6	7.11	9	24	37	75	5.62	<1	0.25	<10	2.02	2476	<2	0.02	12	1880	9	2.10	<5	6	261	<5	<0.01	<10	18	77	<10	80	2
130319	1.4	2.57	160	166	<0.5	5	5.03	3	25	40	78	5.38	<1	0.28	<10	2.22	1973	<2	0.02	11	2050	7	1.55	<5	6	210	<5	<0.01	<10	16	81	<10	93	2
130320	1.6	2.81	559	140	<0.5	5	4.28	13	25	35	91	5.57	<1	0.23	<10	2.41	2085	<2	0.02	12	1923	6	0.97	<5	6	180	<5	<0.01	<10	15	82	<10	120	2
130321	1.9	2.01	387	155	<0.5	5	4.31	9	26	38	87	5.55	<1	0.29	<10	1.55	1691	<2	0.02	13	1876	14	2.92	<5	5	146	<5	<0.01	<10	14	58	<10	96	2
130322	1.4	2.35	341	130	<0.5	5	4.62	8	25	30	92	5.41	<1	0.25	<10	1.92	1771	<2	0.01	12	1844	9	1.83	<5	5	178	<5	<0.01	<10	15	68	<10	95	2
130323	1.3	2.87	214	177	<0.5	7	10.07	5	26	38	93	5.60	<1	0.42	<10	2.10	2887	<2	0.01	12	1969	7	1.58	<5	7	364	<5	<0.01	<10	20	80	<10	82	2
130324	1.3	2.56	253	139	<0.5	6	6.40	6	25	28	90	5.75	<1	0.30	<10	2.04	2077	<2	0.01	12	1954	8	2.09	<5	6	245	<5	<0.01	<10	18	71	<10	96	2
130325	3.0	1.63	786	163	<0.5	189	9.17	19	53	78	506	6.29	13	0.21	13	0.38	996	151	0.04	80	1056	93	2.47	<5	4	128	<5	0.15	<10	<10	45	55	101	19
130326	1.4	2.23	295	139	<0.5	7	4.99	7	26	28	96	5.91	<1	0.30	<10	1.78	1732	<2	0.01	12	2018	11	3.09	<5	5	203	<5	<0.01	<10	17	62	<10	105	3
130327	1.5	1.99	191	109	<0.5	5	6.29	4	20	27	90	4.52	<1	0.25	<10	1.63	2061	<2	0.01	10	1595	7	1.82	<5	5	237	<5	<0.01	<10	11	57	<10	54	2
130328	1.3	2.34	214	128	<0.5	5	5.79	5	24	31	88	5.28	<1	0.30	<10	1.96	2044	<2	0.01	11	1801	8	1.83	<5	6	234	<5	<0.01	<10	17	68	<10	73	2
130329	1.5	2.10	272	120	<0.5	5	6.70	6	22	26	78	4.99	<1	0.24	<10	1.81	2534	<2	0.01	11	1750	10	1.75	<5	6	276	<5	<0.01	<10	19	62	<10	68	2
130330	2.2	1.86	581	153	<0.5	5	6.39	13	24	24	81	5.34	<1	0.29	<10	1.48	2499	<2	0.01	11	1825	15	3.15	<5	6	234	<5	<0.01	<10	19	53	<10	60	2
130331	1.4	2.24	196	109	<0.5	5	6.22	4	20	23	84	4.96	<1	0.25	<10	1.80	2093	<2	0.01	10	1669	7	1.71	<5	5	228	<5	0.01	<10	17	57	<10	65	2
130332	1.5	2.24	224	122	<0.5	5	6.42	5	24	40	91	4.96	<1	0.26	<10	1.85	2092	<2	0.01	13	1808	7	1.86	<5	6	252	<5	0.01	<10	16	67	<10	78	2
130333	1.8	2.04	438	170	<0.5	7	6.00	10	30	37	82	6.64	<1	0.39	<10	1.55	1958	3	0.01	14	2164	16	4.66	<5	6	210	<5	0.01	<10	13	61	<10	108	3
130334	1.6	1.97	479	130	<0.5	5	6.02	11	25	26	83	5.98	<1	0.28	<10	1.64	1930	<2	0.01	12	1772	14	3.96	<5	5	258	<5	0.01	<10	18	55	<10	77	3
130335	1.1	2.77	270	117	<0.5	5	6.01	6	23	31	84	5.43	<1	0.26	<10	2.29	2020	<2	0.01	11	1805	6	1.35	<5	6	264	<5	0.01	<10	17	82	<10	75	2
130336	1.2	2.76	175	109	<0.5	5	6.39	4	24	31	79	5.38	1	0.24	<10	2.25	2100	<2	0.01	11	1701	4	1.23	<5	6	268	<5	0.01	<10	17	82	<10	72	2
130337	1.1	2.91	693	101	<0.5	5	5.80	16	24	31	87	5.46	<1	0.24	<10	2.34	2211	<2	0.01	11	1842	2	0.85	<5	7	218	<5	0.01	<10	17	89	<10	78	2
130338	1.3	2.96	243	95	<0.5	5	5.51	5	23	32	98	5.55	<1	0.24	<10	2.48	2132	<2	0.01	11	1753	4	0.85	<5	7	207	<5	0.01	<10	18	89	<10	82	2
130339	1.6	2.30	219	96	<0.5	5	5.98	5	23	28	88	5.01	<1	0.27	<10	2.01	2150	<2	0.01	11	1696	7	1.50	<5	6	216	<5	<0.01	<10	17	68	<10	70	2
130340	1.7	2.27	307	118	<0.5	5	7.51	7	28	17	104	5.06	<1	0.31	<10	1.73	2783	<2	0.01	16	1250	16	1.77	<5	6	248	<5	<0.01	<10	20	71	<10	98	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3551RJ**

Date : Oct-16-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 31

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130341	1.3	2.43	250	105	<0.5	6	6.23	6	25	28	71	5.50	<1	0.30	<10	1.66	2527	<2	0.01	11	1826	15	1.55	<5	6	226	<5	<0.01	<10	19	63	<10	104	2
130342	0.3	2.56	70	96	<0.5	5	5.96	1	18	34	59	5.21	<1	0.27	<10	1.72	2061	<2	0.01	8	1758	3	0.53	<5	6	211	<5	0.01	<10	16	74	<10	80	2
130343	0.5	2.97	147	97	<0.5	5	6.17	3	24	32	60	5.83	<1	0.26	<10	2.17	2072	<2	0.01	10	1833	4	0.51	<5	7	268	<5	0.02	<10	17	78	<10	92	2
130344	0.2	2.93	53	113	<0.5	5	5.56	1	20	32	51	5.57	<1	0.32	<10	2.02	1908	<2	0.01	9	1863	2	0.30	<5	6	217	<5	0.02	<10	17	78	<10	88	2
130345	0.6	3.07	169	111	<0.5	6	6.12	4	23	44	81	5.57	1	0.31	<10	2.10	2111	<2	0.01	12	1800	3	0.36	<5	6	223	<5	0.02	<10	15	81	<10	90	2
130346	0.6	3.00	116	102	<0.5	7	6.18	2	23	48	76	5.66	1	0.27	<10	2.11	2280	<2	0.01	11	1848	<2	0.36	<5	6	214	<5	0.01	<10	17	82	<10	88	2
130347	1.0	2.50	308	103	<0.5	6	7.49	7	21	34	77	5.04	<1	0.28	<10	1.69	2644	<2	0.01	10	1798	6	1.04	<5	6	214	<5	0.02	<10	18	62	<10	71	2
130348	1.6	2.26	691	104	<0.5	5	6.75	18	21	33	88	4.96	<1	0.29	<10	1.46	2826	<2	0.01	11	1840	23	1.58	<5	5	208	<5	0.03	<10	15	57	<10	128	2
130349	1.8	2.13	652	119	<0.5	6	6.80	17	20	31	69	4.96	<1	0.35	<10	1.30	3119	<2	0.01	8	1687	21	2.04	<5	5	152	<5	0.01	<10	16	59	<10	96	2
130350	2.4	0.12	13	15	<0.5	12	>15.00	<1	1	4	2	0.19	<1	0.04	<10	1.76	69	<2	0.03	<1	88	<2	0.15	<5	<1	5809	<5	<0.01	<10	<10	5	<10	1	<1
130351	2.2	1.06	1111	82	<0.5	5	6.84	29	17	30	56	3.96	<1	0.26	<10	0.65	2643	<2	0.01	8	1461	20	3.07	<5	4	147	<5	0.01	<10	17	32	<10	41	1
130352	1.4	0.71	1055	81	<0.5	<5	8.18	27	15	38	21	3.34	<1	0.24	<10	0.44	2434	<2	0.01	6	1102	33	3.24	<5	3	252	<5	0.02	<10	15	23	<10	76	1
130353	1.7	2.52	385	95	<0.5	5	5.26	9	25	29	75	5.85	<1	0.28	<10	2.05	2512	<2	0.01	10	1926	10	2.40	<5	5	141	<5	0.03	<10	16	66	<10	91	2
130354	1.4	2.61	244	100	<0.5	<5	5.36	6	22	33	67	5.01	<1	0.33	<10	1.86	2549	<2	0.03	10	1703	9	1.67	<5	6	122	<5	0.05	<10	17	68	<10	75	2
130355	1.4	3.86	606	177	<0.5	<5	5.12	15	25	45	77	5.37	<1	0.65	<10	2.11	2692	<2	0.05	11	1904	6	1.50	<5	10	133	<5	0.08	<10	17	110	<10	79	2
130356	1.1	4.34	2322	174	<0.5	<5	4.55	59	24	58	81	5.49	<1	0.65	<10	2.00	2107	<2	0.10	11	1874	14	2.33	<5	12	92	<5	0.09	<10	<10	146	<10	75	3
130357	1.4	5.33	7477	134	<0.5	<5	5.13	197	28	69	96	5.80	1	0.44	<10	2.17	2192	<2	0.15	14	1975	17	2.46	<5	11	107	<5	0.09	<10	<10	164	<10	181	4
130358	1.0	4.48	381	68	<0.5	<5	4.84	9	30	71	89	6.00	<1	0.14	<10	1.91	1987	<2	0.10	14	1930	9	2.08	<5	9	88	<5	0.11	<10	<10	164	<10	123	4
130359	1.8	2.80	158	93	<0.5	<5	4.99	4	25	59	76	5.16	<1	0.27	<10	1.05	2247	<2	0.08	12	1767	11	2.63	<5	8	84	<5	0.07	<10	14	106	<10	92	4
130360	4.8	2.10	305	97	<0.5	<5	6.62	8	23	46	68	5.06	1	0.29	<10	0.74	3272	<2	0.07	11	1620	22	3.78	<5	6	101	<5	0.08	<10	19	72	<10	88	4
130361	9.0	0.97	864	99	<0.5	<5	2.29	22	25	37	51	5.58	<1	0.31	<10	0.44	1604	<2	0.03	13	1825	32	>5.00	<5	5	44	<5	0.05	<10	<10	44	<10	102	4
130362	12.8	1.21	772	72	<0.5	8	4.11	19	30	26	95	7.24	<1	0.38	<10	0.60	3330	<2	0.02	15	1990	27	>5.00	9	5	121	<5	<0.01	<10	24	38	<10	77	3
130363	8.5	1.00	467	67	<0.5	7	3.54	11	28	24	74	6.33	<1	0.35	<10	0.55	2544	<2	0.02	13	1720	30	>5.00	5	5	77	<5	0.01	<10	16	37	<10	87	3
130364	12.2	0.83	714	104	<0.5	5	2.99	18	23	20	91	4.77	1	0.33	<10	0.35	2586	<2	0.02	11	1590	35	4.42	13	4	65	<5	<0.01	<10	13	25	<10	48	2
130365	24.8	0.89	849	105	<0.5	7	9.18	22	15	48	79	4.02	<1	0.29	<10	0.45	7487	<2	0.01	7	1219	91	3.67	19	3	159	<5	0.01	<10	42	29	<10	100	<1
130366	2.9	2.71	633	114	<0.5	7	5.48	16	23	29	81	5.74	<1	0.31	<10	1.58	3455	<2	0.02	10	1943	8	1.36	<5	6	119	<5	<0.01	<10	24	74	<10	70	2
130367	1.7	2.76	673	114	<0.5	6	5.28	17	20	24	67	5.35	<1	0.29	<10	1.76	2849	<2	0.02	9	1591	4	0.87	<5	7	148	<5	0.01	<10	17	86	<10	79	2
130368	2.5	2.75	207	110	<0.5	6	5.79	5	26	25	83	5.05	<1	0.29	<10	1.85	2640	<2	0.02	9	1539	9	0.65	<5	7	158	<5	0.01	<10	18	85	<10	78	2
130369	2.2	2.48	124	98	<0.5	5	5.66	3	22	22	73	4.79	<1	0.24	<10	1.69	2222	<2	0.01	9	1595	6	0.66	<5	6	174	<5	0.02	<10	12	74	<10	71	2
130370	2.2	2.95	119	112	<0.5	5	5.19	2	21	27	81	5.64	<1	0.26	<10	2.11	2560	<2	0.02	8	1734	6	0.69	<5	7	164	<5	0.03	<10	18	93	<10	85	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3551RJ**

Date : Oct-16-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 31

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130371	2.1	2.04	278	89	<0.5	7	11.34	7	12	18	65	4.19	<1	0.23	<10	1.35	3753	<2	0.02	5	1321	11	1.08	<5	5	241	<5	0.02	<10	23	58	<10	70	1
130372	1.4	2.32	174	120	<0.5	<5	5.72	4	21	7	78	4.58	<1	0.27	<10	1.56	3052	<2	0.01	6	1147	6	0.85	<5	4	183	<5	0.07	<10	19	66	<10	77	2
130373	1.3	1.11	679	100	<0.5	<5	10.88	18	15	11	32	2.98	<1	0.24	<10	0.68	3531	<2	0.01	4	801	40	1.74	<5	2	331	<5	0.02	<10	21	30	<10	161	<1
130374	3.4	1.65	446	128	<0.5	<5	3.92	11	23	17	207	4.40	1	0.27	<10	0.98	1650	<2	0.02	9	1418	19	2.14	<5	5	112	<5	0.03	<10	10	50	<10	81	2
130375	<0.2	0.98	6578	23	<0.5	19	5.73	173	167	13	67	3.41	<1	0.05	11	0.23	710	15	0.08	31	1330	12	1.38	<5	1	91	<5	0.06	<10	<10	37	<10	94	10
130376	2.1	1.85	113	142	<0.5	6	9.63	3	19	8	74	4.45	<1	0.25	<10	1.18	3352	<2	0.01	6	1019	11	1.63	<5	3	245	<5	0.02	<10	20	46	<10	74	1
130377	1.9	2.29	135	123	<0.5	6	6.93	3	22	20	52	4.89	<1	0.25	<10	1.56	2993	<2	0.02	9	1569	11	1.41	<5	6	175	<5	0.02	<10	20	78	<10	88	2
130378	1.1	1.91	309	142	<0.5	6	5.72	8	16	3	41	4.21	<1	0.30	<10	0.99	2767	<2	0.02	2	1307	8	1.04	<5	2	152	<5	0.01	<10	16	33	<10	93	1
130379	0.7	1.66	53	158	<0.5	<5	3.70	1	12	3	35	3.63	<1	0.32	<10	0.73	1829	<2	0.02	2	1235	5	0.69	<5	2	101	<5	0.01	<10	12	26	<10	99	1
130380	0.2	1.84	30	151	<0.5	<5	4.73	<1	13	3	12	3.88	<1	0.31	<10	0.82	2168	<2	0.02	2	1204	3	0.47	<5	2	126	<5	0.01	<10	14	28	<10	80	1
130381	<0.2	1.83	50	160	<0.5	<5	4.53	1	12	3	2	3.81	<1	0.31	<10	0.82	2001	<2	0.02	2	1326	3	0.39	<5	2	132	<5	0.02	<10	12	28	<10	72	1
130382	2.2	1.74	76	152	<0.5	<5	4.99	2	13	4	41	4.22	<1	0.27	<10	0.84	2595	<2	0.02	2	1258	14	1.15	<5	2	144	<5	0.03	<10	17	29	<10	142	1
130383	0.5	1.76	24	152	<0.5	<5	5.19	<1	14	4	3	3.98	<1	0.26	<10	0.90	2709	<2	0.02	2	1227	5	0.74	<5	2	165	<5	0.06	<10	16	28	<10	73	1
130384	1.5	1.74	441	160	<0.5	<5	5.31	12	15	4	35	4.29	<1	0.28	<10	0.89	3309	<2	0.02	2	1309	38	1.31	<5	2	177	<5	0.03	<10	20	30	<10	169	1
130385	2.2	1.72	1250	158	<0.5	<5	5.78	33	16	4	46	4.16	<1	0.28	<10	0.95	3804	<2	0.02	3	1242	79	1.49	<5	2	213	<5	0.04	<10	19	39	<10	190	1
130386	1.7	1.40	174	149	<0.5	<5	6.05	4	15	4	33	3.99	<1	0.28	<10	0.75	3362	<2	0.02	2	1206	25	2.22	<5	2	188	<5	0.07	<10	20	26	<10	60	1
130387	1.8	2.22	161	157	<0.5	<5	5.73	4	16	4	53	4.63	<1	0.28	<10	1.31	3636	<2	0.02	2	1386	19	1.14	<5	3	181	<5	0.04	<10	19	37	<10	139	1
130388	1.8	2.22	183	172	<0.5	<5	5.60	5	16	4	58	4.49	<1	0.31	<10	1.25	3769	<2	0.02	2	1349	46	0.88	<5	2	165	<5	0.04	<10	19	37	<10	165	1
130389	2.0	1.81	165	150	<0.5	6	6.89	4	16	5	82	4.78	<1	0.27	<10	1.03	4012	<2	0.03	6	1452	37	1.43	<5	2	232	<5	0.01	<10	24	35	<10	176	1
130390	2.2	1.88	95	142	<0.5	6	7.83	2	15	5	120	4.63	<1	0.25	<10	1.18	3870	<2	0.03	4	1414	13	1.07	<5	3	189	<5	0.01	<10	23	30	<10	122	1
130391	1.3	1.57	74	161	<0.5	5	6.66	2	16	5	67	4.04	<1	0.28	<10	0.89	3410	<2	0.03	5	1472	32	0.99	<5	2	176	<5	0.02	<10	19	24	<10	150	1
130392	2.6	1.53	2397	165	<0.5	5	4.98	65	15	9	84	4.78	<1	0.30	<10	0.85	3552	<2	0.02	4	1463	519	1.80	<5	2	157	<5	0.02	<10	20	34	11	696	1
130393	0.8	1.57	749	179	<0.5	<5	5.85	20	12	4	33	3.81	<1	0.32	11	0.79	3285	<2	0.03	2	1474	84	0.61	<5	2	159	<5	0.02	<10	17	22	<10	270	1
130394	1.3	1.75	314	173	<0.5	5	4.44	9	12	7	46	5.21	<1	0.32	11	0.85	3089	2	0.03	2	1226	83	1.55	<5	1	129	<5	0.02	<10	17	23	<10	302	2
130395	2.4	1.11	1193	165	<0.5	<5	6.33	34	11	8	75	3.67	<1	0.32	<10	0.51	3508	2	0.02	3	1175	304	1.88	<5	1	188	<5	0.02	<10	18	23	12	716	1
130396	0.5	1.29	46	205	<0.5	<5	4.57	1	7	6	20	2.93	<1	0.37	14	0.53	2682	<2	0.03	1	1109	75	0.67	<5	1	148	<5	0.01	<10	<10	13	<10	94	1
130397	0.7	1.20	68	219	<0.5	<5	4.22	2	7	6	26	2.94	<1	0.38	15	0.47	2513	<2	0.03	1	1092	36	0.98	<5	1	145	<5	0.01	<10	<10	13	<10	138	1
130398	0.4	1.15	1075	206	<0.5	<5	3.73	27	9	6	26	3.10	<1	0.35	13	0.48	2010	<2	0.03	1	1198	13	1.13	<5	1	133	<5	0.01	<10	<10	13	<10	87	1
130399	0.3	0.93	727	151	<0.5	5	4.27	18	8	5	14	2.90	<1	0.27	<10	0.46	2220	<2	0.02	1	1176	12	1.25	<5	1	159	<5	0.01	<10	<10	10	<10	65	1
130400	<0.2	0.09	57	20	<0.5	14	>15.00	2	<1	2	2	0.10	<1	0.04	<10	2.08	65	<2	0.01	<1	89	<2	0.04	<5	<1	4994	<5	<0.01	<10	<10	1	<10	1	<1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3551RJ

Date : Oct-16-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 31

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130401	1.0	1.80	1247	167	<0.5	6	5.58	31	16	7	47	5.05	<1	0.31	<10	1.08	3014	<2	0.02	5	1325	14	1.64	<5	3	203	<5	0.03	<10	13	39	<10	66	2
130402	1.2	1.90	99	125	<0.5	6	8.63	2	18	8	50	4.83	<1	0.24	<10	1.27	3389	<2	0.02	6	1101	9	1.53	<5	3	317	<5	0.04	<10	13	55	<10	55	1
130403	1.3	2.08	98	154	<0.5	7	6.72	2	24	9	41	5.61	<1	0.29	<10	1.32	2955	<2	0.02	8	1203	22	2.06	<5	4	251	<5	0.06	<10	11	61	<10	81	2
130404	0.9	2.55	75	127	<0.5	<5	7.44	1	24	16	48	5.74	<1	0.26	<10	1.89	3365	<2	0.02	14	1156	10	1.26	<5	7	260	<5	0.10	<10	13	86	<10	66	2
130405	1.3	3.11	40	96	<0.5	<5	7.67	1	29	45	97	6.20	1	0.20	<10	2.72	3006	<2	0.02	27	910	6	0.87	<5	13	288	<5	0.17	<10	<10	138	<10	72	3
130406	1.8	3.01	102	116	<0.5	9	8.89	2	29	39	110	6.53	<1	0.29	<10	2.53	3686	<2	0.03	28	981	6	1.28	<5	11	295	<5	0.04	<10	15	108	<10	72	2
130407	2.0	3.26	82	103	<0.5	<5	6.36	2	31	43	108	5.82	1	0.21	<10	2.88	4203	<2	0.02	28	918	5	0.90	<5	14	248	<5	0.17	<10	16	141	<10	75	2
130408	2.6	3.24	554	118	<0.5	6	6.27	14	30	34	115	6.26	<1	0.23	<10	2.82	4501	<2	0.02	23	1058	13	1.38	<5	10	216	<5	0.08	<10	16	126	<10	104	2
130409	1.6	1.81	2813	119	<0.5	8	5.40	72	18	7	71	4.57	<1	0.25	<10	1.23	3317	<2	0.02	7	1137	37	1.37	<5	3	177	<5	0.01	<10	11	43	<10	360	1
130410	1.7	1.57	100	118	<0.5	8	5.01	9	17	7	93	4.61	<1	0.28	<10	0.85	2935	<2	0.03	7	1400	153	1.82	<5	3	145	<5	0.02	<10	10	32	13	761	1
130411	1.3	1.83	87	148	<0.5	<5	5.12	2	14	8	45	4.75	<1	0.33	<10	0.92	2983	<2	0.03	4	1335	45	1.32	<5	2	148	<5	0.03	<10	18	33	<10	81	1
130412	0.7	1.77	5732	158	<0.5	<5	4.46	145	15	5	24	4.66	<1	0.34	11	1.07	2410	<2	0.03	4	1559	25	1.65	<5	2	153	<5	0.03	<10	<10	35	<10	97	2
130413	1.2	1.83	5808	150	<0.5	5	5.98	146	15	11	36	4.75	<1	0.35	10	1.05	3497	<2	0.02	4	1695	76	1.43	<5	2	193	<5	0.03	<10	20	39	<10	197	1
130414	1.8	1.89	986	166	<0.5	<5	4.14	25	16	6	81	4.47	<1	0.35	10	1.07	2970	<2	0.03	4	1722	12	1.04	<5	2	129	<5	0.04	<10	17	41	<10	101	1
130415	1.5	1.53	1354	152	<0.5	5	10.46	34	18	12	46	4.89	<1	0.36	10	0.83	4119	<2	0.02	4	1685	33	2.46	<5	2	385	<5	0.05	<10	22	36	<10	70	1
130416	0.9	2.05	185	147	<0.5	<5	4.96	4	16	7	43	4.78	<1	0.34	12	1.13	3081	<2	0.03	4	1466	4	0.77	<5	3	151	<5	0.04	<10	17	40	<10	78	1
130417	1.1	1.84	147	150	<0.5	5	4.52	3	15	12	50	4.49	<1	0.32	11	0.92	2642	<2	0.03	4	1535	9	0.96	<5	3	154	<5	0.01	<10	15	37	<10	80	1
130418	0.8	1.98	69	148	<0.5	5	4.89	2	14	10	39	4.79	<1	0.34	11	1.09	2821	<2	0.03	4	1515	6	1.07	<5	3	167	<5	0.03	<10	16	40	<10	105	1
130419	0.9	1.65	250	133	<0.5	<5	7.71	6	11	29	37	3.77	<1	0.31	<10	0.91	3627	<2	0.02	3	1299	7	1.01	<5	2	373	<5	0.03	<10	20	33	<10	97	1
130420	1.3	1.85	2139	157	<0.5	7	6.28	54	15	17	42	5.00	<1	0.38	<10	1.08	3500	<2	0.02	4	1617	24	2.09	<5	3	303	<5	0.01	<10	22	41	<10	98	1
130421	1.2	2.11	126	174	<0.5	5	2.30	3	16	12	69	4.98	<1	0.39	11	1.22	2211	<2	0.03	4	1873	13	1.06	<5	3	85	<5	0.02	<10	<10	47	<10	102	2
130422	1.4	1.33	2416	131	<0.5	6	4.91	65	17	14	30	5.02	<1	0.38	<10	0.71	2951	<2	0.03	3	1728	67	3.13	<5	2	163	<5	0.01	<10	19	32	<10	160	2
130423	1.1	1.41	3819	141	<0.5	5	5.07	95	14	12	33	4.58	<1	0.39	<10	0.79	3194	<2	0.03	2	1578	56	2.41	<5	1	165	<5	0.01	<10	20	23	<10	162	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3613-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment32**
Attn: **Sue Deane**

Oct-21-08

We hereby certify the following assay of 22 core samples submitted Oct-06-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121718	0.03	0.04	2.4
121719	0.04		1.0
121720	0.08		0.4
121721	0.02		0.2
121722	0.01		<0.1
121723	0.02		0.1
121724	0.01		0.2
121725	6.63		2.6
121726	0.01		0.1
121727	0.01	0.01	0.3
121728	0.02		0.2
121729	<0.01		0.8
121730	<0.01		<0.1
121731	<0.01		<0.1
121732	<0.01		<0.1
121733	0.01		<0.1
121734	<0.01		<0.1
121735	0.01		<0.1
121736	<0.01		<0.1
121737	0.01	0.01	<0.1
121738	0.01		<0.1
121739	0.03		<0.1
*0211	2.23		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3613-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment32**
Attn: **Sue Deane**

Oct-21-08

We hereby certify the following assay of 22 core samples submitted Oct-06-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121740	0.02	0.02	0.4
121741	0.01		<0.1
121742	<0.01		<0.1
121743	<0.01		<0.1
121744	<0.01		<0.1
121745	<0.01		<0.1
121746	0.59		4.1
121747	0.40		4.0
121748	0.04		0.5
121749	0.06	0.05	0.6
121750	<0.01		<0.1
121751	0.02		0.2
121752	<0.01		<0.1
121753	0.01		<0.1
121754	0.01		0.3
121755	<0.01		0.3
121756	0.01		0.1
121757	0.01		0.2
121758	<0.01		<0.1
121759	<0.01	0.01	<0.1
121760	<0.01		0.1
121761	<0.01		<0.1
*0211	2.22		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3613-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment32**
Attn: **Sue Deane**

Oct-21-08

We hereby certify the following assay of 22 core samples submitted Oct-06-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121762	<0.01	<0.01	<0.1
121763	<0.01		<0.1
121764	0.15		<0.1
121765	<0.01		<0.1
121766	0.07		<0.1
121767	0.06		<0.1
121768	0.02		<0.1
121769	0.01		<0.1
121770	0.03		<0.1
121771	0.04	0.05	<0.1
121772	0.06		<0.1
121773	0.03		<0.1
121774	0.03		<0.1
121775	1.84		186.0
121776	0.01		<0.1
121777	0.03		<0.1
121778	0.07		<0.1
121779	0.07		<0.1
121780	0.03		<0.1
121781	0.04	0.04	<0.1
121782	0.02		<0.1
121783	<0.01		<0.1
*0211	2.20		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3613-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment32**
Attn: **Sue Deane**

Oct-21-08

We hereby certify the following assay of 22 core samples submitted Oct-06-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121784	0.02	0.03	0.6
121785	0.04		0.9
121786	0.07		0.8
121787	0.03		0.2
121788	0.20		0.5
121789	0.03		<0.1
121790	0.02		<0.1
121791	0.02		<0.1
121792	0.05		<0.1
121793	0.03	0.03	0.1
121794	0.04		<0.1
121795	0.02		0.2
121796	0.06		<0.1
121797	0.02		<0.1
121798	0.07		<0.1
121799	0.02		0.4
121800	<0.01		<0.1
121801	0.01		0.3
121802	0.08		0.3
121803	<0.01	0.01	<0.1
121804	0.02		0.2
121805	0.05		0.3
*0211	2.23		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3613-RA5

Company: **Ascot Resources Ltd**
 Project: **Dilworth/shipment32**
 Attn: **Sue Deane**

Oct-21-08

We hereby certify the following assay of 22 core samples submitted Oct-06-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
121806	0.03	0.04	0.9	
121807	0.01		0.8	
121808	0.06		0.8	
121809	0.19		0.8	
121810	0.02		0.2	
121811	<0.01		<0.1	
121812	0.01		<0.1	
121813	<0.01		2.1	
121814	<0.01		0.6	
121815	<0.01	0.02	0.2	
121816	0.07		1.2	
121817	0.05		1.9	
121818	0.08		1.0	
121819	0.02		1.4	
121820	0.04		0.6	
121821	0.03		0.7	
121822	0.02		0.2	
121823	0.02		0.3	
121824	0.06		0.4	
121825	0.13	0.13	>200	793.0
121826	0.06		1.8	
121827	0.04		1.0	
*0211	2.21			
*CCu-1c				128.6
*BLANK	<0.01			<0.1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3613-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment32**
Attn: **Sue Deane**

Oct-21-08

We hereby certify the following assay of 22 core samples submitted Oct-06-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121828	0.03	0.03	1.0
121829	0.02		0.5
121830	0.04		0.5
121831	0.05		0.7
121832	1.48		1.5
121833	0.03		0.9
121834	0.02		0.5
121835	0.03		0.6
121836	0.02		<0.1
121837	0.02	0.01	<0.1
121851	0.20		0.9
121852	0.23		1.9
121853	0.38		2.1
121854	1.13		4.4
121855	0.25		1.1
121856	0.17		1.4
121857	0.08		5.4
121858	0.46		2.0
121859	0.24		2.2
121860	0.27	0.28	3.3
121861	0.11		3.3
121862	0.13		9.1
*0211	2.20		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3613-RA7

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment32**
Attn: **Sue Deane**

Oct-21-08

We hereby certify the following assay of 22 core samples submitted Oct-06-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121863	0.62	0.65	2.3
121864	0.18		2.5
121865	0.32		3.0
121866	0.74		6.7
121867	1.38		5.9
130424	0.02		0.7
130425	0.35		<0.1
130426	0.02		0.8
130426A	0.01		0.7
130427	<0.01	0.01	0.6
130428	0.01		0.3
130429	0.02		1.0
130430	0.08		0.9
130431	0.06		0.6
130432	0.14		1.0
130433	0.25		1.6
130434	0.03		0.2
130435	0.04		0.8
130436	0.06		2.2
130437	0.08	0.08	0.9
130438	0.01		0.4
130439	0.04		3.4
*0211	2.23		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3613-RA8

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment32**
Attn: **Sue Deane**

Oct-21-08

We hereby certify the following assay of 22 core samples submitted Oct-06-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130440	0.11	0.11	1.0
130441	0.13		<0.1
130442	0.07		<0.1
130443	0.11		<0.1
130444	0.08		<0.1
130445	0.12		<0.1
130446	0.08		<0.1
130447	0.12		<0.1
130448	0.11		<0.1
130449	0.09	0.09	<0.1
130450	0.01		2.8
130451	0.16		<0.1
130452	0.06		<0.1
130453	0.03		<0.1
130454	0.02		<0.1
130455	0.05		<0.1
130456	0.03		<0.1
130457	0.01		<0.1
130458	0.02		<0.1
130459	0.05	0.05	<0.1
130460	0.03		<0.1
130461	0.02		<0.1
*0211	2.21		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3613-RA9

Company: **Ascot Resources Ltd**
 Project: **Dilworth/shipment32**
 Attn: **Sue Deane**

Oct-21-08

We hereby certify the following assay of 10 core samples submitted Oct-06-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
130462	0.02	0.02	<0.1	
130463	0.09		<0.1	
130464	0.04		<0.1	
130465	0.03		<0.1	
130466	0.01		<0.1	
130467	0.01		<0.1	
130468	0.01		<0.1	
130469	0.02		<0.1	
130470	0.02		<0.1	
130471	0.01	0.01	<0.1	
130472	0.05		<0.1	
130473	0.05		<0.1	
130474	0.02		<0.1	
130475	0.13		>200	806.0
130476	0.02		<0.1	
130477	0.27		<0.1	
130478	0.07		<0.1	
130479	0.06		0.5	
130480	0.05		<0.1	
130481	0.08	0.09	<0.1	
130482	0.05		<0.1	
130483	0.07		<0.1	
*0211	2.23			
*CCu-1c				129.9
*BLANK	<0.01			<0.1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3613-RA10

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment32**
Attn: **Sue Deane**

Oct-21-08

We hereby certify the following assay of 22 core samples submitted Oct-06-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130484	0.03	0.03	<0.1
130485	0.02		<0.1
130486	0.02		<0.1
130487	0.02		<0.1
130488	<0.01		<0.1
130489	0.01		<0.1
139541	0.13		<0.1
139542	0.07		0.3
139543	0.12		2.6
139544	0.08	0.08	<0.1
139545	0.16		3.8
139546	0.18		3.7
139547	0.05		<0.1
139548	0.29		0.5
139549	0.08		<0.1
139550	0.14		0.5
139551	0.34		14.9
139552	0.06		<0.1
*0211	2.19		
*BLANK	<0.01		

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3613RJ

Date : Oct-21-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment32

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121718	2.4	2.39	255	80	<0.5	6	6.42	5	29	49	90	6.55	1	0.17	<10	2.10	1762	<2	0.01	15	1856	19	2.19	<5	12	198	<5	0.02	<10	<10	182	<10	96	3
121719	1.0	2.38	185	80	<0.5	7	6.53	4	27	51	82	6.41	<1	0.21	<10	1.96	1814	<2	0.01	14	1766	26	1.91	<5	10	233	<5	0.01	<10	<10	139	<10	116	3
121720	0.4	3.04	86	55	<0.5	7	8.82	4	34	102	97	7.34	<1	0.11	<10	2.54	2102	2	0.01	21	1656	19	0.91	<5	18	305	<5	0.01	<10	<10	219	<10	132	3
121721	0.2	3.43	84	44	<0.5	5	8.93	11	35	106	96	7.82	1	0.05	<10	3.12	2136	<2	0.01	21	1723	39	0.63	<5	25	331	<5	0.04	<10	<10	283	<10	152	4
121722	<0.2	3.89	68	59	<0.5	<5	5.84	1	35	97	83	8.14	<1	0.04	<10	4.37	1645	<2	0.01	20	1735	12	0.60	<5	28	238	<5	0.12	<10	<10	287	<10	103	5
121723	<0.2	3.00	65	45	<0.5	<5	7.99	5	35	118	88	7.01	1	0.04	<10	3.22	1880	<2	0.02	21	1767	28	0.62	<5	19	291	<5	0.14	<10	<10	260	<10	114	5
121724	0.2	2.97	78	63	<0.5	<5	6.09	3	36	125	72	7.05	<1	0.04	<10	3.39	1843	<2	0.02	22	1787	24	0.80	<5	17	236	<5	0.14	<10	<10	241	<10	177	5
121725	2.6	1.50	769	146	<0.5	183	8.91	16	48	73	484	6.48	15	0.19	12	0.38	894	152	0.04	74	1018	87	2.17	<5	3	118	<5	0.11	<10	<10	41	53	92	17
121726	<0.2	3.29	19	50	<0.5	<5	7.63	<1	35	255	121	6.50	2	0.03	<10	3.92	2105	<2	0.01	34	1781	11	0.24	<5	17	327	<5	0.12	<10	<10	231	<10	83	5
121727	0.3	3.29	19	52	<0.5	7	9.52	<1	32	292	92	6.47	1	0.03	<10	3.59	1908	<2	0.01	36	1624	18	0.21	<5	26	403	<5	0.02	<10	<10	224	<10	95	3
121728	0.2	2.79	46	81	<0.5	5	11.12	1	26	247	65	6.00	<1	0.12	<10	2.39	2183	2	0.03	30	1762	20	0.49	<5	19	318	<5	0.06	<10	<10	178	<10	142	3
121729	0.8	2.15	31	91	<0.5	<5	5.17	<1	34	189	64	4.81	<1	0.10	<10	1.53	1338	6	0.06	38	2002	14	0.31	<5	8	133	<5	0.16	<10	<10	127	<10	56	5
121730	<0.2	1.14	<5	90	<0.5	<5	2.31	<1	11	54	4	2.35	<1	0.20	<10	0.85	468	4	0.04	6	985	3	0.01	<5	3	109	<5	0.14	<10	<10	47	<10	47	9
121731	<0.2	1.08	<5	2291	<0.5	<5	4.59	<1	8	45	5	1.98	<1	0.22	17	0.69	856	<2	0.04	6	956	3	0.14	<5	2	279	<5	0.01	<10	<10	28	<10	38	4
121732	<0.2	0.60	<5	85	<0.5	<5	2.20	<1	3	50	7	1.07	<1	0.22	21	0.27	316	<2	0.04	3	496	8	0.06	<5	1	90	5	<0.01	<10	<10	11	<10	19	7
121733	<0.2	0.57	<5	89	<0.5	<5	1.65	<1	4	51	2	1.20	1	0.21	19	0.29	247	<2	0.04	3	516	7	0.14	<5	1	72	5	<0.01	<10	<10	11	<10	21	7
121734	<0.2	0.87	<5	106	<0.5	<5	2.74	<1	6	44	<1	1.81	<1	0.23	17	0.59	439	<2	0.03	4	900	5	0.13	<5	1	161	5	<0.01	<10	<10	17	<10	35	4
121735	<0.2	1.39	<5	160	0.6	<5	4.34	<1	11	88	15	3.12	<1	0.28	11	1.21	1278	4	0.03	12	1062	8	0.10	<5	9	256	<5	<0.01	<10	<10	76	<10	53	4
121736	<0.2	1.99	29	176	<0.5	6	4.90	1	13	9	34	5.27	<1	0.30	10	1.43	1916	<2	0.02	2	1694	26	0.69	<5	4	144	<5	<0.01	<10	<10	67	<10	157	2
121737	<0.2	1.22	72	160	<0.5	<5	2.05	2	14	10	47	4.67	<1	0.31	10	0.68	1251	<2	0.02	3	1672	32	1.03	<5	3	63	<5	<0.01	<10	<10	39	<10	179	2
121738	<0.2	1.15	72	153	<0.5	<5	2.57	2	12	6	34	4.46	<1	0.30	10	0.77	1662	<2	0.01	2	1625	15	0.65	<5	3	70	<5	<0.01	<10	<10	35	<10	201	2
121739	<0.2	0.40	150	138	<0.5	5	11.73	3	10	19	22	3.28	<1	0.30	<10	0.38	2266	<2	0.01	2	1190	13	1.38	<5	2	547	<5	<0.01	<10	<10	13	<10	100	1
121740	0.4	0.68	74	137	0.7	6	3.48	2	16	20	46	4.71	<1	0.42	<10	0.49	1693	<2	0.01	4	1760	22	1.26	<5	3	115	<5	<0.01	<10	<10	22	<10	120	2
121741	<0.2	0.44	30	487	0.6	6	4.22	2	14	26	14	3.85	<1	0.26	20	0.72	1058	<2	0.02	11	2202	28	0.19	<5	4	188	<5	<0.01	<10	<10	11	<10	192	3
121742	<0.2	0.83	5	1206	<0.5	<5	2.38	<1	9	33	6	2.34	<1	0.26	20	0.56	480	<2	0.03	4	1078	8	0.08	<5	3	107	<5	<0.01	<10	<10	27	<10	60	4
121743	<0.2	1.38	11	500	<0.5	<5	2.44	<1	16	53	38	3.64	<1	0.24	24	1.18	667	<2	0.04	13	2011	36	0.18	<5	5	89	0.05	<10	<10	57	<10	80	5	
121744	<0.2	1.62	<5	869	<0.5	<5	2.81	<1	16	60	8	3.93	<1	0.19	28	1.51	674	<2	0.04	16	2080	5	0.04	<5	5	128	0.05	<10	<10	61	<10	96	5	
121745	<0.2	1.16	5	1037	<0.5	<5	3.14	<1	15	53	5	3.73	<1	0.22	23	1.34	785	<2	0.04	14	1918	8	0.10	<5	4	179	0.06	<10	<10	52	<10	91	5	
121746	4.1	1.00	97	207	0.5	7	3.20	3	26	39	59	6.37	<1	0.32	<10	0.54	4563	9	0.01	10	2135	25	0.85	<5	5	191	<0.01	<10	19	42	<10	169	2	
121747	4.0	1.27	190	127	<0.5	8	1.84	6	19	44	73	7.38	<1	0.35	<10	0.61	2213	4	0.01	13	1834	93	2.55	<5	5	83	<0.01	<10	16	41	<10	268	3	

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3613RJ

Date : Oct-21-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment32

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121748	0.5	0.81	162	140	0.5	7	2.01	4	26	31	44	5.99	<1	0.35	<10	0.54	1748	<2	0.01	10	2062	18	0.83	<5	4	74	<0.01	<10	10	42	<10	118	2	
121749	0.6	1.02	86	235	0.5	7	4.11	2	24	37	64	5.97	<1	0.37	<10	0.57	1974	3	0.01	10	2233	26	1.13	<5	5	147	<0.01	<10	<10	53	<10	120	3	
121750	<0.2	0.12	5	21	<0.5	11	>15.00	<1	1	5	3	0.23	<1	0.06	<10	2.19	99	<2	0.01	<1	141	<2	0.05	<5	<1	4666	<0.01	<10	<10	4	<10	3	<1	
121751	0.2	2.75	31	90	0.5	8	5.64	1	29	113	67	6.12	<1	0.29	<10	2.54	1755	<2	0.01	23	1982	14	0.52	<5	13	286	<0.01	<10	14	139	<10	114	3	
121752	<0.2	1.28	5	339	<0.5	<5	3.16	<1	10	38	9	2.64	<1	0.23	20	1.00	481	<2	0.04	6	1413	11	0.12	<5	2	193	<0.01	<10	<10	35	<10	70	3	
121753	<0.2	1.52	8	285	<0.5	<5	3.19	<1	13	47	17	3.20	<1	0.22	17	1.19	686	<2	0.03	9	1462	20	0.18	<5	4	134	0.01	<10	<10	52	<10	76	3	
121754	0.3	3.36	38	153	<0.5	9	9.23	1	29	134	85	6.45	<1	0.15	<10	3.02	2262	<2	0.01	24	1745	28	0.43	<5	16	242	0.01	<10	11	180	<10	133	3	
121755	0.3	3.40	33	165	<0.5	7	6.28	1	31	157	90	6.60	<1	0.10	<10	3.22	1688	<2	0.01	26	2143	17	0.38	<5	18	194	0.01	<10	11	215	<10	135	3	
121756	<0.2	3.50	37	89	<0.5	8	6.14	1	37	150	112	6.95	1	0.09	<10	3.24	1810	<2	0.01	29	2056	19	0.54	<5	21	202	0.02	<10	12	218	<10	124	3	
121757	0.2	2.98	34	129	<0.5	5	5.97	1	35	204	130	6.27	<1	0.13	<10	2.51	1699	<2	0.01	35	2161	13	0.39	<5	21	202	0.05	<10	13	219	<10	97	4	
121758	<0.2	2.34	<5	223	<0.5	6	3.63	<1	21	77	22	5.27	<1	0.10	36	2.08	986	<2	0.03	18	2924	6	0.07	<5	7	144	0.01	<10	<10	84	<10	125	5	
121759	<0.2	2.19	<5	148	<0.5	7	3.62	<1	18	68	14	4.76	<1	0.15	30	1.82	868	<2	0.03	16	2654	4	0.02	<5	7	158	0.01	<10	<10	67	<10	116	4	
121760	<0.2	3.47	25	216	<0.5	8	4.01	1	34	179	84	7.34	1	0.36	<10	2.75	1722	<2	0.04	29	2257	15	0.58	<5	20	184	0.03	<10	14	217	<10	143	3	
121761	<0.2	1.24	<5	107	<0.5	<5	3.02	<1	10	34	18	2.34	<1	0.31	14	0.72	607	3	0.04	4	1051	7	0.38	<5	2	135	<0.01	<10	<10	27	<10	50	5	
121762	<0.2	1.03	<5	187	0.8	<5	3.87	<1	12	151	13	3.30	<1	0.27	14	1.17	652	<2	<0.01	9	1666	16	0.10	6	5	155	<5	<0.01	<10	17	108	<10	94	5
121763	<0.2	0.23	<5	29	<0.5	<5	1.23	<1	2	125	11	0.43	<1	0.21	<10	0.08	169	2	<0.01	2	89	16	0.07	<5	<1	40	<5	<0.01	<10	28	8	<10	15	10
121764	<0.2	0.15	<5	20	<0.5	<5	0.39	<1	1	108	13	0.38	<1	0.17	<10	0.03	117	<2	<0.01	1	32	34	0.09	<5	<1	14	<5	<0.01	<10	20	6	<10	37	6
121765	<0.2	0.62	8	60	0.6	<5	3.64	<1	9	162	14	2.35	<1	0.20	<10	0.73	1033	<2	<0.01	9	626	24	0.12	5	7	149	<5	<0.01	<10	11	91	<10	53	9
121766	<0.2	2.59	54	184	<0.5	<5	4.01	1	33	212	112	6.00	<1	0.37	<10	2.47	1541	<2	0.14	25	1664	41	1.23	15	14	108	<5	0.12	<10	<10	315	<10	127	5
121767	<0.2	1.82	34	100	<0.5	<5	4.21	1	23	123	64	4.97	<1	0.28	<10	1.49	1265	<2	0.06	13	1557	34	1.28	11	8	93	<5	0.06	<10	<10	197	<10	108	4
121768	<0.2	2.16	31	44	<0.5	<5	6.60	<1	26	193	79	5.13	<1	0.13	<10	2.31	1499	<2	0.05	22	1273	36	0.72	12	11	144	<5	0.03	<10	<10	244	<10	78	4
121769	<0.2	2.32	69	64	<0.5	<5	5.30	2	34	233	95	5.83	<1	0.17	<10	2.39	1379	<2	0.04	29	1652	40	1.09	13	12	145	<5	0.04	<10	<10	289	<10	106	5
121770	<0.2	2.30	33	47	<0.5	<5	4.59	<1	28	159	89	5.64	<1	0.17	<10	2.44	1347	<2	0.04	19	1681	51	0.86	13	10	121	<5	0.06	<10	<10	252	<10	69	5
121771	<0.2	2.27	45	59	<0.5	<5	6.91	1	25	168	76	5.48	<1	0.14	<10	2.52	1511	<2	0.04	18	1364	44	0.80	11	11	163	<5	0.03	<10	<10	247	<10	75	4
121772	<0.2	2.17	66	58	<0.5	<5	6.56	1	26	161	93	5.35	<1	0.18	<10	2.13	1708	<2	0.04	18	1443	43	0.95	13	9	154	<5	0.04	<10	<10	213	<10	79	4
121773	<0.2	2.82	26	120	<0.5	<5	5.97	<1	32	197	93	6.26	<1	0.14	<10	3.03	1596	<2	0.05	24	1578	48	0.55	15	14	164	<5	0.06	<10	<10	302	<10	112	5
121774	<0.2	3.06	24	51	<0.5	<5	6.11	1	35	226	92	6.57	<1	0.12	<10	3.40	1555	<2	0.03	25	1628	44	0.43	15	18	172	<5	0.10	<10	<10	336	<10	143	5
121775	186.2	0.65	204	194	<0.5	49	6.01	7	16	39	3509	3.18	3	0.15	<10	0.20	562	69	0.04	35	537	204	1.23	250	2	154	<5	0.07	<10	18	57	25	242	12
121776	<0.2	3.03	21	73	<0.5	<5	6.51	<1	34	283	96	6.57	<1	0.12	<10	3.66	1510	<2	0.04	27	1937	51	0.54	17	18	157	<5	0.14	<10	<10	358	<10	100	6
121777	<0.2	2.58	29	53	<0.5	<5	11.28	<1	30	204	93	5.89	<1	0.13	<10	2.86	1993	<2	0.03	24	1583	41	0.59	13	14	207	<5	0.09	<10	<10	301	<10	60	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3613RJ

Date : Oct-21-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment32

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121778	<0.2	2.49	69	62	<0.5	<5	7.97	1	32	179	93	5.99	<1	0.19	<10	2.50	1556	<2	0.02	23	1726	47	1.08	15	12	193	<5	0.08	<10	<10	266	<10	61	5
121779	<0.2	2.32	50	48	<0.5	<5	7.39	1	29	173	77	5.50	<1	0.19	<10	2.29	1438	<2	0.03	23	1561	40	0.85	14	11	165	<5	0.10	<10	<10	230	<10	60	5
121780	<0.2	2.46	36	61	<0.5	<5	6.31	<1	31	191	98	5.90	<1	0.23	<10	2.20	1430	<2	0.03	23	1876	46	0.89	16	11	162	<5	0.11	<10	<10	247	<10	89	5
121781	<0.2	2.24	42	52	<0.5	<5	8.14	1	25	151	72	5.06	<1	0.17	<10	2.14	1858	<2	0.03	16	1495	37	0.53	13	10	187	<5	0.09	<10	<10	219	<10	78	4
121782	<0.2	2.24	46	69	<0.5	<5	5.57	1	26	82	76	5.34	<1	0.22	<10	1.96	1573	2	0.03	10	1590	37	0.73	12	6	119	<5	0.11	<10	<10	176	<10	79	5
121783	<0.2	1.66	18	121	<0.5	<5	2.94	<1	26	109	22	4.21	<1	0.08	15	1.80	689	<2	0.10	14	2412	23	0.07	16	6	81	<5	0.41	<10	43	161	<10	122	21
121784	0.6	2.57	34	64	<0.5	9	5.85	1	23	52	92	5.28	1	0.21	<10	1.73	1997	3	0.01	14	1552	19	0.65	<5	6	159	<5	0.04	<10	<10	83	<10	73	3
121785	0.9	2.76	53	250	<0.5	9	3.63	1	26	95	106	5.83	1	0.27	<10	1.91	1944	<2	0.01	21	1663	22	0.75	<5	9	107	<5	0.03	<10	<10	117	<10	92	3
121786	0.8	2.35	59	192	<0.5	11	5.11	2	19	40	72	5.80	3	0.35	<10	1.31	2109	7	0.01	10	1700	30	1.19	<5	5	138	<5	0.02	<10	14	76	<10	123	2
121787	0.2	2.32	23	81	<0.5	11	5.16	1	15	7	38	5.21	1	0.31	10	1.33	2014	2	0.01	4	1466	19	0.73	<5	3	176	<5	0.02	<10	<10	61	<10	98	2
121788	0.5	2.08	32	84	<0.5	7	3.96	1	16	8	53	5.01	1	0.28	<10	1.04	1768	2	0.02	3	1485	32	0.92	<5	3	171	<5	0.02	<10	<10	60	<10	109	2
121789	<0.2	1.48	11	82	<0.5	<5	4.46	1	9	16	28	3.43	<1	0.22	11	0.73	1537	<2	0.02	1	1274	10	0.37	<5	3	134	<5	0.05	<10	<10	42	<10	75	2
121790	<0.2	1.61	13	97	<0.5	<5	3.75	<1	10	14	30	3.68	<1	0.30	<10	0.77	1427	<2	0.02	1	1352	19	0.54	<5	3	129	<5	0.08	<10	<10	42	<10	70	3
121791	<0.2	1.77	17	124	<0.5	<5	4.06	1	13	11	36	3.88	1	0.37	10	0.82	1592	<2	0.02	2	1443	14	0.61	<5	4	143	<5	0.14	<10	<10	49	<10	69	3
121792	<0.2	2.00	28	112	<0.5	<5	4.98	1	16	9	48	4.75	<1	0.30	<10	1.03	1951	<2	0.02	2	1526	16	0.90	<5	4	274	<5	0.16	<10	<10	56	<10	87	3
121793	<0.2	2.01	61	104	<0.5	<5	4.62	2	14	10	45	4.52	<1	0.35	<10	0.98	1890	<2	0.01	2	1343	40	0.79	<5	3	132	<5	0.09	<10	<10	45	<10	155	3
121794	<0.2	1.89	33	100	<0.5	<5	4.67	2	13	16	50	4.11	<1	0.30	<10	0.88	1621	2	0.02	2	1484	35	0.59	<5	2	134	<5	0.09	<10	<10	43	<10	145	3
121795	0.2	1.71	34	105	<0.5	<5	4.58	2	11	13	42	3.75	<1	0.31	<10	0.79	1463	<2	0.02	2	1324	45	0.56	<5	2	126	<5	0.07	<10	<10	40	<10	142	2
121796	<0.2	1.87	48	276	<0.5	<5	4.82	4	11	25	37	3.41	<1	0.29	<10	0.80	1467	2	0.07	3	1347	16	0.62	<5	3	112	<5	0.14	<10	<10	44	<10	283	4
121797	<0.2	1.73	<5	594	<0.5	<5	2.21	<1	24	61	15	3.86	1	0.09	19	1.38	617	<2	0.04	13	2259	2	0.17	<5	7	52	<5	0.37	<10	<10	83	<10	106	13
121798	<0.2	1.77	<5	39	<0.5	<5	2.17	<1	20	55	21	3.90	1	0.09	19	1.46	695	2	0.04	11	2007	5	0.02	<5	6	46	<5	0.36	<10	<10	73	<10	92	20
121799	0.4	2.51	31	128	<0.5	<5	3.70	1	10	14	45	3.38	<1	0.31	<10	0.76	1408	3	0.17	1	1246	16	0.56	<5	4	105	<5	0.12	<10	<10	50	<10	77	3
121800	<0.2	0.11	<5	<10	<0.5	11	>15.00	<1	1	8	29	0.14	<1	0.02	<10	6.64	114	<2	0.01	2	171	<2	<0.01	6	<1	2454	<5	<0.01	<10	<10	4	<10	10	1
121801	0.3	2.06	46	129	<0.5	<5	3.15	1	10	25	29	3.54	<1	0.36	<10	0.90	1590	2	0.10	1	1268	11	0.60	<5	3	110	<5	0.13	<10	<10	45	<10	74	3
121802	0.3	2.16	63	125	<0.5	<5	3.87	1	12	13	51	3.83	1	0.32	<10	1.05	1526	<2	0.10	1	1332	17	0.73	<5	4	142	<5	0.12	<10	<10	50	<10	80	3
121803	<0.2	2.04	14	78	<0.5	<5	2.94	<1	22	61	31	4.10	<1	0.16	21	1.48	913	2	0.08	12	2490	8	0.22	<5	5	71	<5	0.36	<10	<10	76	<10	123	28
121804	0.2	1.89	69	110	<0.5	<5	3.49	2	11	31	40	4.00	1	0.29	<10	0.87	1821	2	0.05	2	1351	19	0.71	<5	3	114	<5	0.09	<10	<10	51	<10	89	2
121805	0.3	1.76	63	129	<0.5	<5	4.38	2	12	17	36	3.92	1	0.40	<10	0.79	1883	<2	0.02	2	1317	32	0.93	<5	2	146	<5	0.11	<10	11	44	<10	105	3
121806	0.9	1.78	163	152	<0.5	<5	4.47	4	16	16	45	4.73	<1	0.46	<10	0.83	1733	<2	0.02	3	1686	46	1.42	<5	3	170	<5	0.04	<10	<10	60	<10	141	2
121807	0.8	1.60	190	127	<0.5	<5	5.38	5	19	20	45	4.80	<1	0.37	<10	0.86	1875	<2	0.02	3	1629	40	2.04	<5	3	147	<5	0.13	<10	<10	66	<10	222	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3613RJ

Date : Oct-21-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment32

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121808	0.8	1.64	1413	284	<0.5	<5	4.88	30	19	12	47	5.36	<1	0.35	<10	0.88	1777	<2	0.02	3	1650	26	2.41	<5	3	155	<5	0.10	<10	<10	70	<10	91	3
121809	0.8	1.68	3675	142	<0.5	<5	5.01	78	15	15	31	4.85	<1	0.39	<10	0.90	2007	2	0.01	2	1507	36	1.68	<5	3	175	<5	0.02	<10	10	64	<10	137	2
121810	0.2	1.21	250	139	<0.5	<5	5.27	6	13	13	20	4.02	<1	0.34	<10	0.61	1915	<2	0.02	1	1381	22	1.77	<5	3	199	<5	0.01	<10	<10	31	<10	111	2
121811	<0.2	1.35	141	169	<0.5	<5	3.89	7	13	15	26	3.90	<1	0.37	<10	0.63	1367	<2	0.02	2	1496	16	1.62	<5	3	128	<5	0.02	<10	<10	36	<10	259	2
121812	<0.2	1.76	63	139	<0.5	<5	4.83	1	15	11	28	4.84	<1	0.32	<10	0.88	1842	<2	0.02	2	1506	14	1.02	<5	3	180	<5	0.01	<10	<10	53	<10	120	2
121813	2.1	2.16	70	138	<0.5	<5	5.18	7	20	12	159	6.19	<1	0.32	<10	1.02	2412	<2	0.02	4	1662	310	1.15	<5	3	213	<5	0.01	<10	11	73	12	801	2
121814	0.6	2.25	52	161	<0.5	<5	5.17	1	24	12	61	6.33	<1	0.33	<10	1.08	2645	<2	0.03	6	1723	12	0.99	<5	5	248	<5	0.06	<10	12	97	<10	84	3
121815	0.2	1.54	191	141	<0.5	<5	5.64	4	15	62	9	3.97	<1	0.31	<10	0.77	2199	<2	0.01	4	1096	22	0.63	<5	2	421	<5	0.09	<10	<10	30	<10	80	2
121816	1.2	2.21	660	118	<0.5	<5	7.74	15	31	108	79	5.27	<1	0.25	<10	1.78	2244	<2	0.01	21	1689	75	0.95	<5	12	225	<5	0.05	<10	<10	154	<10	206	2
121817	1.9	2.76	354	74	<0.5	<5	7.81	8	34	131	100	6.62	<1	0.23	<10	2.30	2418	<2	0.01	28	1860	82	1.34	<5	12	259	<5	0.03	<10	17	147	<10	198	3
121818	1.0	1.70	356	64	<0.5	<5	12.88	7	24	95	62	4.73	<1	0.23	<10	1.17	3155	<2	0.01	19	1487	16	1.39	<5	7	319	<5	0.01	<10	19	85	<10	85	1
121819	1.4	2.29	120	49	<0.5	<5	12.08	7	27	115	118	5.50	<1	0.12	<10	1.92	3164	<2	0.01	19	1462	124	0.54	<5	13	300	<5	0.15	<10	17	145	12	688	2
121820	0.6	2.76	128	63	<0.5	<5	6.99	3	37	122	83	6.55	<1	0.21	<10	2.43	1820	<2	0.01	23	2055	13	0.97	<5	13	197	<5	0.17	<10	14	159	<10	131	3
121821	0.7	2.54	116	63	<0.5	<5	8.48	2	34	125	97	6.39	<1	0.17	<10	2.02	1873	<2	0.01	23	1881	18	0.93	<5	17	250	<5	0.13	<10	<10	197	<10	103	3
121822	0.2	2.58	77	59	<0.5	<5	9.08	2	35	158	91	6.32	1	0.06	<10	2.47	1822	<2	0.01	24	1929	4	0.39	<5	19	223	<5	0.21	<10	<10	251	<10	96	9
121823	0.3	2.80	193	70	<0.5	<5	9.38	4	31	137	95	6.93	<1	0.06	<10	2.70	2227	<2	0.02	22	1984	27	0.79	<5	21	210	<5	0.11	<10	<10	270	<10	110	6
121824	0.4	2.97	132	73	<0.5	<5	5.50	2	41	146	102	7.76	1	0.08	<10	3.30	1777	<2	0.03	25	2292	12	1.82	<5	20	139	<5	0.21	<10	<10	285	<10	98	8
121825	>200.0	0.65	670	197	<0.5	105	0.63	22	8	23	8352	2.35	8	0.17	<10	0.62	294	647	0.03	5	503	981	1.19	1895	2	88	<5	0.06	<10	<10	21	<10	1033	2
121826	1.8	2.90	135	80	<0.5	<5	5.93	2	31	121	127	7.19	<1	0.12	<10	2.51	1931	<2	0.02	22	2165	42	1.11	<5	20	154	<5	0.03	<10	11	245	<10	101	4
121827	1.0	2.51	124	69	<0.5	5	7.32	4	27	132	84	6.79	<1	0.13	<10	2.04	2054	<2	0.01	20	2186	61	1.46	<5	18	221	<5	0.01	<10	<10	228	<10	248	3
121828	1.0	2.68	101	88	<0.5	5	8.07	2	25	153	110	6.42	1	0.13	<10	2.20	2203	<2	0.01	22	1923	51	1.06	<5	20	261	<5	0.01	<10	<10	239	<10	116	3
121829	0.5	2.67	59	62	<0.5	8	8.77	1	26	133	119	5.75	<1	0.05	<10	2.29	2178	<2	0.01	22	1881	10	0.68	<5	23	240	<5	0.01	<10	<10	252	<10	74	3
121830	0.5	3.45	139	54	<0.5	10	7.47	3	30	140	94	7.32	2	0.09	<10	3.01	1953	<2	0.02	24	1932	26	1.33	<5	21	183	<5	0.01	<10	<10	253	<10	123	4
121831	0.7	2.96	92	58	<0.5	6	5.59	2	29	114	82	5.77	<1	0.16	<10	2.79	1866	<2	0.01	24	1862	26	0.74	<5	14	157	<5	0.02	<10	<10	187	<10	137	3
121832	1.5	1.15	137	69	<0.5	<5	3.58	7	15	68	45	3.62	1	0.17	<10	0.73	746	<2	0.01	12	1177	94	1.91	<5	5	85	<5	<0.01	<10	<10	61	15	869	2
121833	0.9	2.92	97	376	<0.5	6	2.61	2	33	99	117	6.94	<1	0.27	<10	2.04	1409	<2	0.01	24	2065	24	1.50	<5	12	71	<5	0.01	<10	<10	141	<10	105	3
121834	0.5	2.29	89	132	<0.5	5	2.82	2	30	87	111	5.70	<1	0.37	<10	1.28	1326	<2	0.01	26	1994	32	1.15	<5	10	77	<5	0.01	<10	<10	98	<10	146	2
121835	0.6	2.41	91	166	<0.5	6	2.51	4	18	31	81	6.88	<1	0.35	<10	0.95	1590	<2	0.01	10	621	132	1.32	<5	5	113	<5	0.01	<10	10	58	<10	305	3
121836	<0.2	2.43	72	144	<0.5	<5	4.06	2	25	13	50	5.88	<1	0.30	16	1.38	1625	<2	0.01	7	597	50	0.76	<5	5	113	<5	0.02	<10	<10	42	<10	127	3
121837	<0.2	2.37	37	169	<0.5	<5	2.50	1	21	11	38	5.55	<1	0.31	13	1.32	1440	<2	0.02	6	658	30	0.60	<5	6	78	<5	0.15	<10	<10	61	<10	116	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3613RJ

Date : Oct-21-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment32

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121851	0.9	1.87	10	125	<0.5	<5	5.98	2	17	12	206	4.47	<1	0.27	<10	1.23	1794	42	0.01	3	1222	9	0.47	<5	4	267	<5	0.02	<10	<10	57	<10	276	3
121852	1.9	2.79	11	126	<0.5	<5	7.19	2	23	16	313	7.10	<1	0.23	<10	2.10	2646	32	0.02	4	1317	9	0.62	<5	6	259	<5	0.04	<10	13	88	<10	412	4
121853	2.1	2.58	15	75	<0.5	<5	5.89	3	21	11	273	5.99	<1	0.23	<10	1.71	2317	38	0.02	4	1271	10	0.55	<5	5	170	<5	0.10	<10	<10	82	<10	386	4
121854	4.4	2.26	25	82	<0.5	<5	5.57	7	33	9	543	5.49	<1	0.13	<10	1.94	2012	35	0.02	7	1117	11	0.85	<5	4	177	<5	0.11	<10	<10	76	14	626	4
121855	1.1	1.89	9	124	<0.5	<5	3.91	3	16	7	247	5.00	<1	0.30	10	1.04	1796	25	0.02	2	1429	12	0.41	<5	5	198	<5	0.02	<10	<10	65	<10	393	2
121856	1.4	2.02	22	152	<0.5	<5	2.91	4	16	5	245	5.10	<1	0.37	11	1.06	1698	28	0.02	2	1441	11	0.45	<5	4	98	<5	0.01	<10	<10	60	<10	433	2
121857	5.4	1.74	104	156	<0.5	5	7.79	4	16	5	264	4.50	<1	0.33	10	0.96	2731	41	0.01	1	1330	48	0.92	<5	3	246	<5	<0.01	<10	<10	48	<10	276	2
121858	2.0	2.01	25	89	<0.5	<5	4.54	2	15	5	277	4.97	<1	0.33	<10	1.01	2051	47	0.01	2	1303	16	0.66	<5	4	100	<5	0.04	<10	<10	66	<10	307	2
121859	2.2	2.23	37	113	<0.5	<5	2.88	3	16	5	285	5.64	<1	0.38	<10	1.06	1958	57	0.01	2	1501	11	0.69	<5	4	65	<5	0.05	<10	<10	64	<10	396	2
121860	3.3	2.05	53	105	<0.5	<5	4.00	7	18	7	271	5.07	<1	0.38	<10	1.06	2313	66	0.01	3	1333	18	0.91	<5	4	89	<5	0.04	<10	10	64	12	617	2
121861	3.3	2.17	121	113	<0.5	<5	4.68	6	17	6	307	6.19	<1	0.26	<10	1.21	2947	28	<0.01	3	1343	61	1.44	<5	4	75	<5	0.01	<10	13	77	<10	494	2
121862	9.1	1.94	106	140	<0.5	<5	3.37	35	20	8	491	5.60	<1	0.40	<10	1.00	2206	49	<0.01	3	1449	3022	1.95	<5	4	70	<5	0.01	<10	<10	58	63	3843	2
121863	2.3	2.05	36	131	<0.5	<5	3.54	4	19	20	333	5.67	<1	0.31	<10	1.06	2077	156	0.01	2	1354	15	0.66	<5	4	107	<5	0.02	<10	10	69	<10	377	2
121864	2.5	2.03	43	105	<0.5	<5	4.80	4	16	6	245	5.46	<1	0.24	<10	1.08	2639	78	0.01	2	1321	38	0.57	<5	4	124	<5	0.01	<10	12	76	<10	454	2
121865	3.0	1.89	46	103	<0.5	<5	4.44	5	16	4	353	5.40	<1	0.24	<10	1.09	2266	48	0.01	2	1449	187	0.73	<5	4	126	<5	0.01	<10	11	70	<10	495	2
121866	6.7	1.75	96	129	<0.5	<5	4.66	56	16	7	466	5.16	<1	0.23	<10	0.93	2350	112	0.01	2	1327	1194	1.36	<5	3	122	<5	0.01	<10	11	66	110	6721	2
121867	5.9	2.24	88	62	<0.5	<5	6.99	5	25	5	601	5.99	<1	0.16	<10	1.43	3123	117	0.01	5	1305	19	0.57	<5	6	238	<5	0.01	<10	15	91	<10	432	2
130424	0.7	0.61	105	137	<0.5	<5	8.72	3	14	6	49	4.06	<1	0.28	<10	0.26	2677	<2	0.02	1	1534	77	4.41	<5	1	278	<5	0.06	<10	13	13	<10	245	2
130425	<0.2	1.11	7723	25	<0.5	19	6.25	162	181	14	77	3.83	<1	0.05	13	0.25	757	19	0.10	34	1545	12	1.47	<5	2	104	<5	0.06	<10	<10	42	<10	100	13
130426	0.8	0.91	143	115	<0.5	<5	4.41	3	30	4	42	6.01	<1	0.42	<10	0.41	1408	<2	0.02	4	2280	46	>5.00	<5	3	151	<5	0.13	<10	<10	28	<10	94	3
130426A	0.7	0.99	38	147	<0.5	<5	4.70	1	29	6	58	5.84	<1	0.39	<10	0.58	1527	<2	0.03	3	2138	32	>5.00	<5	3	195	<5	0.14	<10	10	29	<10	210	3
130427	0.6	1.26	67	102	<0.5	<5	4.96	3	24	4	55	5.69	<1	0.26	<10	0.89	2246	<2	0.02	3	1956	91	4.29	<5	3	132	<5	0.07	<10	13	37	<10	415	3
130428	0.3	1.91	37	139	<0.5	<5	4.51	<1	28	4	70	6.94	<1	0.31	<10	1.44	2438	<2	0.02	4	2206	8	3.98	<5	5	154	<5	0.04	<10	12	89	<10	103	3
130429	1.0	1.11	98	128	<0.5	6	4.80	2	33	8	77	5.74	<1	0.37	<10	0.85	2082	<2	0.02	4	2441	101	>5.00	<5	4	223	<5	0.02	<10	12	66	<10	169	4
130430	0.9	1.23	190	143	<0.5	<5	4.10	4	20	13	54	5.15	<1	0.30	<10	0.82	1942	<2	0.02	2	1767	39	3.56	<5	3	226	<5	<0.01	<10	12	35	<10	87	2
130431	0.6	1.15	172	157	<0.5	<5	4.60	3	18	9	46	4.69	<1	0.33	<10	0.72	2234	<2	0.02	2	1699	32	2.99	<5	2	171	<5	<0.01	<10	13	25	<10	53	2
130432	1.0	0.58	319	117	<0.5	<5	4.14	9	18	27	14	5.18	<1	0.31	<10	0.24	1580	<2	0.02	2	1287	88	>5.00	<5	2	173	<5	<0.01	<10	10	14	<10	390	2
130433	1.6	0.55	338	136	<0.5	<5	4.68	10	17	15	29	4.36	<1	0.31	<10	0.19	2002	<2	0.02	1	1362	141	4.39	<5	1	166	<5	0.02	<10	10	13	10	703	2
130434	0.2	1.63	98	190	<0.5	<5	5.23	2	19	9	35	5.05	<1	0.34	<10	0.80	2688	<2	0.02	1	1655	13	1.84	<5	2	224	<5	0.04	<10	18	35	<10	111	2
130435	0.8	1.20	95	181	<0.5	<5	5.42	3	16	18	49	3.70	<1	0.32	<10	0.55	2563	<2	0.02	1	1238	115	1.41	<5	2	249	<5	0.05	<10	11	27	<10	211	1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3613RJ

Date : Oct-21-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment32

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130436	2.2	0.57	167	134	<0.5	<5	6.21	8	13	32	124	2.69	<1	0.23	<10	0.22	1767	<2	0.01	1	877	247	2.09	<5	2	198	<5	0.02	<10	<10	13	10	769	1
130437	0.9	0.93	187	137	<0.5	<5	8.26	4	13	13	25	3.96	<1	0.22	<10	0.47	2593	<2	0.01	1	1190	118	2.46	<5	2	247	<5	0.02	<10	12	20	<10	163	2
130438	0.4	1.22	53	127	<0.5	<5	9.11	1	12	21	13	3.86	<1	0.24	<10	0.69	3407	<2	0.01	<1	1218	70	1.44	<5	2	609	<5	0.06	<10	15	27	<10	98	2
130439	3.4	1.19	107	147	<0.5	<5	8.17	27	13	9	179	4.17	<1	0.28	<10	0.58	2987	<2	0.02	1	1295	840	2.23	<5	2	243	<5	0.05	<10	<10	26	52	3154	2
130440	1.0	1.11	189	157	<0.5	<5	4.36	11	14	8	160	3.81	<1	0.29	<10	0.57	2296	<2	0.02	<1	1147	1735	2.41	12	2	139	<5	0.01	<10	<10	61	14	1013	3
130441	<0.2	0.77	190	126	<0.5	<5	5.22	5	9	26	78	3.03	<1	0.24	<10	0.35	2218	<2	0.04	<1	970	147	2.06	7	1	158	<5	0.01	<10	<10	47	<10	67	2
130442	<0.2	1.21	102	143	<0.5	<5	3.99	2	9	<1	15	3.32	<1	0.26	<10	0.64	2171	<2	0.05	<1	1188	90	1.24	6	1	134	<5	0.01	<10	<10	54	<10	86	2
130443	<0.2	0.84	172	157	<0.5	<5	3.86	4	14	8	32	3.58	<1	0.28	<10	0.39	1935	<2	0.04	<1	1232	85	2.68	7	1	130	<5	0.01	<10	<10	54	<10	141	2
130444	<0.2	1.07	123	162	<0.5	<5	3.10	5	11	9	45	3.21	<1	0.28	<10	0.53	1842	<2	0.04	<1	1140	153	1.50	7	1	109	<5	0.01	<10	<10	51	<10	391	2
130445	<0.2	0.91	182	143	<0.5	<5	3.34	5	12	14	22	3.32	<1	0.23	<10	0.54	1814	<2	0.03	<1	860	59	2.12	8	1	123	<5	<0.01	<10	<10	54	<10	127	2
130446	<0.2	1.28	92	181	<0.5	<5	1.91	2	15	11	27	4.10	<1	0.31	<10	0.76	1604	<2	0.03	<1	1190	34	1.74	8	2	72	<5	<0.01	<10	<10	65	<10	79	3
130447	<0.2	0.65	226	89	<0.5	<5	2.22	6	19	7	23	4.11	<1	0.35	<10	0.38	1140	<2	0.03	<1	1333	116	3.45	11	2	97	<5	<0.01	<10	<10	53	<10	174	3
130448	<0.2	0.43	202	175	<0.5	<5	2.90	5	14	15	17	2.77	<1	0.32	<10	0.23	1124	<2	0.02	<1	971	80	2.29	8	2	114	<5	<0.01	<10	<10	36	<10	106	2
130449	<0.2	0.36	165	138	<0.5	<5	6.60	4	12	7	22	2.22	<1	0.27	<10	0.25	2051	2	0.03	<1	762	35	1.47	8	2	241	<5	<0.01	<10	<10	29	<10	41	1
130450	2.8	0.04	6	11	<0.5	12		<1	1	4	<1	0.04	<1	0.02	<10	1.31	30	<2	<0.01	<1	59	<2	0.08	<5	<1		<5	<0.01	<10	<10	1	<10	1	<1
130451	<0.2	0.46	230	176	<0.5	<5	4.30	6	16	10	17	3.80	<1	0.31	<10	0.49	1803	<2	0.04	<1	1019	48	2.79	10	2	204	<5	<0.01	<10	<10	58	<10	118	3
130452	<0.2	0.90	80	132	<0.5	<5	5.64	2	9	7	10	3.41	<1	0.23	<10	0.65	1932	<2	0.03	<1	931	54	1.34	8	2	215	<5	<0.01	<10	<10	68	<10	90	2
130453	<0.2	1.46	64	128	<0.5	<5	4.55	4	13	2	48	4.11	<1	0.23	<10	0.87	1790	<2	0.03	<1	1148	298	1.49	9	2	184	<5	<0.01	<10	<10	82	<10	351	3
130454	<0.2	1.63	35	149	<0.5	<5	5.28	<1	15	8	23	4.16	<1	0.26	<10	0.86	1703	4	<0.01	<1	1282	22	1.17	13	2	206	<5	<0.01	<10	<10	82	<10	48	3
130455	<0.2	1.55	91	145	<0.5	<5	3.91	2	16	2	34	4.40	<1	0.27	<10	0.83	1299	<2	0.04	<1	1237	21	1.83	8	2	140	<5	0.01	<10	<10	77	<10	82	3
130456	<0.2	1.59	67	150	<0.5	<5	4.81	1	16	3	31	4.01	<1	0.28	<10	0.87	1887	<2	0.03	<1	1171	25	1.32	8	3	202	<5	0.01	<10	<10	83	<10	99	3
130457	<0.2	2.09	32	150	<0.5	<5	3.36	<1	17	<1	30	4.67	<1	0.25	<10	1.21	1632	<2	0.03	<1	1264	22	0.90	9	3	140	<5	0.01	<10	<10	99	<10	77	4
130458	<0.2	2.07	31	147	<0.5	<5	3.61	<1	18	<1	34	4.90	<1	0.26	<10	1.09	1632	<2	0.04	<1	1309	35	1.17	10	3	139	<5	0.01	<10	<10	95	<10	166	3
130459	<0.2	1.71	70	136	<0.5	<5	3.88	2	17	<1	37	4.43	<1	0.24	<10	0.99	1733	<2	0.03	<1	1262	24	1.51	9	3	149	<5	0.01	<10	<10	85	<10	196	3
130460	<0.2	1.89	70	145	<0.5	<5	3.49	5	17	<1	34	4.99	<1	0.26	<10	1.02	1966	<2	0.03	<1	1320	58	1.65	9	3	125	<5	0.01	<10	<10	89	13	864	3
130461	<0.2	2.06	82	160	<0.5	<5	3.92	2	18	<1	39	4.91	<1	0.28	<10	1.12	2237	<2	0.04	<1	1402	50	1.17	8	3	133	<5	0.01	<10	<10	95	<10	338	3
130462	<0.2	2.41	51	205	<0.5	<5	5.03	1	19	<1	41	4.96	<1	0.38	<10	1.25	2330	<2	0.05	<1	1396	31	0.88	10	4	171	<5	0.01	<10	<10	105	<10	125	3
130463	<0.2	2.06	44	185	<0.5	<5	4.90	2	17	<1	75	4.44	<1	0.34	<10	1.08	2366	<2	0.03	<1	1403	213	1.02	10	3	164	<5	0.01	<10	<10	92	<10	271	3
130464	<0.2	1.97	53	187	<0.5	<5	4.53	1	15	<1	48	4.58	<1	0.33	<10	1.00	2305	<2	0.04	<1	1318	30	1.28	10	3	154	<5	0.01	<10	<10	95	<10	263	3
130465	<0.2	2.25	37	186	<0.5	<5	4.40	1	16	<1	36	4.71	<1	0.35	<10	1.10	2045	<2	0.02	<1	1329	33	0.79	9	4	153	<5	0.01	<10	<10	94	<10	183	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3613RJ

Date : Oct-21-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment32

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130466	<0.2	2.35	24	183	<0.5	<5	5.64	<1	19	<1	49	5.04	<1	0.32	<10	1.06	2013	<2	<0.01	<1	1334	27	0.70	10	4	199	<5	0.01	<10	<10	104	<10	53	3
130467	<0.2	2.35	22	168	<0.5	<5	4.70	<1	15	2	61	4.92	<1	0.32	<10	1.06	1578	<2	<0.01	<1	1360	26	0.70	10	4	179	<5	0.01	<10	<10	99	<10	41	3
130468	<0.2	1.99	20	175	<0.5	<5	4.62	<1	13	2	38	4.27	<1	0.32	<10	0.97	1369	<2	<0.01	<1	1298	21	0.58	8	4	167	<5	0.01	<10	<10	85	<10	30	3
130469	<0.2	1.51	42	182	<0.5	<5	4.60	<1	20	5	22	4.81	<1	0.33	<10	0.88	1524	<2	<0.01	<1	1345	26	2.18	9	4	151	<5	<0.01	<10	<10	84	<10	25	3
130470	<0.2	1.09	28	105	<0.5	<5	2.97	<1	11	11	42	5.00	<1	0.39	<10	0.69	1259	<2	<0.01	<1	1370	17	3.50	9	3	123	<5	<0.01	<10	<10	70	<10	21	3
130471	<0.2	0.72	17	58	<0.5	<5	1.19	<1	19	16	34	5.44	<1	0.44	<10	0.36	510	<2	<0.01	<1	1348	22	>5.00	10	3	54	<5	<0.01	<10	<10	74	<10	19	4
130472	<0.2	0.40	54	117	<0.5	<5	6.02	2	15	20	34	4.02	<1	0.29	<10	0.26	2163	<2	0.03	<1	931	125	3.71	11	3	456	<5	<0.01	<10	<10	55	<10	207	3
130473	<0.2	1.17	51	214	<0.5	<5	2.94	1	18	7	53	5.01	<1	0.44	<10	0.79	1424	<2	0.03	<1	1434	38	1.80	13	3	139	<5	<0.01	<10	<10	80	<10	115	3
130474	<0.2	1.79	54	200	<0.5	<5	4.29	1	39	2	56	5.21	<1	0.34	<10	0.86	1896	<2	0.04	<1	1305	39	2.05	19	3	133	<5	0.01	<10	<10	99	<10	144	4
130475	>200.0	0.63	524	174	<0.5	35	0.50	21	7	24	7438	2.09	5	0.17	<10	0.55	268	524	0.04	<1	243	836	1.05	1776	2	80	<5	0.06	<10	<10	<1	<10	866	3
130476	<0.2	2.03	38	209	<0.5	<5	4.54	1	28	<1	71	5.04	<1	0.35	<10	0.88	2125	2	0.02	<1	1317	34	1.21	17	3	145	<5	0.02	<10	<10	95	<10	121	4
130477	<0.2	2.09	49	212	<0.5	<5	5.31	2	22	<1	57	5.20	<1	0.37	<10	0.89	2566	<2	0.03	<1	1365	143	1.31	13	3	171	<5	0.06	<10	<10	95	<10	252	4
130478	<0.2	1.89	83	191	<0.5	<5	5.02	5	36	<1	61	5.50	<1	0.34	<10	0.98	2365	<2	0.02	<1	1310	84	2.43	11	3	155	<5	0.08	<10	<10	99	10	691	4
130479	0.5	1.75	83	172	<0.5	<5	6.04	7	19	<1	66	4.65	<1	0.30	<10	0.92	2361	<2	0.01	<1	1219	70	1.88	10	3	185	<5	0.10	<10	<10	94	14	900	4
130480	<0.2	1.42	121	159	<0.5	<5	3.95	3	27	3	37	4.82	<1	0.38	<10	0.67	1842	<2	<0.01	<1	1413	39	2.90	16	3	126	<5	0.08	<10	<10	86	<10	74	4
130481	<0.2	0.73	97	139	<0.5	5	12.79	3	12	3	15	3.16	<1	0.27	<10	0.34	3719	<2	0.02	<1	725	31	2.28	7	2	522	<5	0.02	<10	<10	53	<10	115	2
130482	<0.2	1.92	56	165	<0.5	<5	5.31	1	21	<1	77	4.72	<1	0.28	<10	1.05	2492	<2	<0.01	<1	1252	23	1.22	10	4	209	<5	0.13	<10	<10	123	<10	106	5
130483	<0.2	1.59	38	176	<0.5	<5	6.86	2	16	<1	247	3.55	<1	0.31	<10	0.80	2927	<2	0.03	<1	1111	1315	0.61	10	4	213	<5	0.12	<10	<10	89	<10	242	3
130484	<0.2	1.97	39	199	<0.5	<5	5.79	1	16	<1	46	4.49	<1	0.38	<10	0.89	2421	<2	0.02	<1	1189	55	0.91	9	3	165	<5	0.06	<10	<10	98	<10	113	3
130485	<0.2	1.24	18	97	<0.5	<5	3.23	<1	17	9	44	5.26	<1	0.42	<10	0.42	1256	<2	<0.01	<1	1385	25	3.69	9	2	102	<5	0.02	<10	<10	81	<10	37	4
130486	<0.2	1.02	46	148	<0.5	<5	7.02	1	15	<1	40	4.22	<1	0.37	<10	0.33	2613	<2	<0.01	<1	1139	23	2.98	8	2	184	<5	0.01	<10	<10	63	<10	42	3
130487	<0.2	1.52	20	113	<0.5	<5	3.46	<1	20	8	45	5.09	<1	0.44	<10	0.67	1844	<2	0.01	<1	1382	48	3.35	11	2	116	<5	0.04	<10	<10	81	<10	72	4
130488	<0.2	1.46	22	135	<0.5	<5	4.36	<1	21	7	40	4.70	<1	0.32	<10	0.82	2038	<2	<0.01	<1	1338	23	2.95	9	2	137	<5	0.02	<10	<10	83	<10	30	3
130489	<0.2	1.42	27	122	<0.5	<5	4.82	<1	27	6	60	5.21	<1	0.31	<10	0.74	2020	<2	<0.01	<1	1464	25	3.51	11	2	134	<5	0.01	<10	<10	89	<10	25	4
139541	<0.2	1.21	115	120	<0.5	<5	0.22	3	11	29	17	4.55	<1	0.21	10	0.64	567	<2	<0.01	1	1156	27	1.39	15	4	7	<5	<0.01	<10	<10	82	<10	62	4
139542	0.3	0.80	110	109	<0.5	<5	0.15	2	8	44	21	4.04	<1	0.18	<10	0.35	339	<2	<0.01	<1	895	24	1.26	15	3	5	<5	<0.01	<10	<10	66	<10	47	4
139543	2.6	0.60	138	105	<0.5	<5	0.13	3	6	78	14	3.28	<1	0.15	<10	0.25	473	2	<0.01	<1	376	22	0.68	13	2	5	<5	<0.01	<10	<10	45	<10	37	3
139544	<0.2	1.03	135	140	<0.5	<5	0.16	3	8	41	10	3.94	<1	0.21	<10	0.43	522	<2	<0.01	<1	847	21	1.20	11	2	5	<5	<0.01	<10	<10	56	<10	53	4
139545	3.8	0.44	241	127	<0.5	<5	0.19	6	7	50	8	3.46	<1	0.19	<10	0.13	196	3	<0.01	<1	860	34	1.84	13	2	7	<5	<0.01	<10	<10	44	<10	45	3
139546	3.7	0.58	172	123	<0.5	<5	0.59	4	7	45	8	3.85	<1	0.20	<10	0.23	406	<2	<0.01	<1	728	30	2.23	12	2	23	<5	<0.01	<10	<10	53	<10	45	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment32

Sample type: core

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3613RJ

Date : Oct-21-08

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
139547	<0.2	0.69	68	110	<0.5	<5	0.18	2	8	49	14	3.33	<1	0.19	14	0.23	416	<2	<0.01	<1	1006	23	0.87	12	2	6	<5	<0.01	<10	<10	50	<10	58	3
139548	0.5	0.93	136	111	<0.5	<5	0.19	3	16	39	18	3.77	<1	0.21	12	0.45	502	<2	<0.01	<1	1020	27	1.53	11	2	6	<5	<0.01	<10	<10	52	<10	75	3
139549	<0.2	1.08	130	198	<0.5	<5	0.17	3	13	23	16	3.48	<1	0.20	13	0.53	558	<2	<0.01	<1	1130	21	0.70	9	3	7	<5	<0.01	<10	<10	56	<10	81	3
139550	0.5	1.01	213	138	<0.5	<5	0.23	5	19	45	17	4.05	<1	0.21	10	0.50	604	2	<0.01	<1	1152	42	1.45	11	3	9	<5	<0.01	<10	<10	65	<10	88	4
139551	14.9	0.21	212	63	<0.5	<5	0.01	6	2	91	28	3.05	<1	0.13	<10	0.03	109	8	<0.01	<1	161	89	0.11	14	1	3	<5	<0.01	<10	<10	35	<10	150	3
139552	<0.2	0.89	134	95	<0.5	<5	0.27	3	5	31	15	3.85	<1	0.18	<10	0.34	460	<2	<0.01	<1	1010	24	0.25	12	2	9	<5	<0.01	<10	<10	64	<10	56	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3613-SG1

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment32**
Attn: **Sue Deane**

Oct-21-08

We *hereby certify* the following geochemical analysis of 22 soil samples submitted Oct-06-08

Sample Name	Au ppb
5000E 2550N	27
5000E 2575N	4
5000E 2600N	48
5000E 2625N	38
5000E 2650N	860
5000E 2675N	110
5000E 2700N	60
5000E 2725N	40
5000E 2750N	124
5000E 2775N	9
5000E 2800N	12
5025E 2550N	1710
5025E 2575N	6
5025E 2600N	1024
5025E 2625N	52
5025E 2650N	14
5025E 2675N	22
5025E 2700N	74
5025E 2725N	10
5025E 2750N	69
5025E 2775N	36
5025E 2800N	48
*0211	2238
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3613-SG2

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment32**
Attn: **Sue Deane**

Oct-21-08

We *hereby certify* the following geochemical analysis of 22 soil samples submitted Oct-06-08

Sample Name	Au ppb
5050E 2550N	66
5050E 2575N	36
5050E 2600N	82
5050E 2625N	208
5050E 2650N	144
5050E 2675N	16
5050E 2700N	88
5050E 2725N	220
5050E 2750N	16
5050E 2775N	48
5050E 2800N	128
5075E 2300N	44
5075E 2325N	342
5075E 2350N	12
5075E 2375N	360
5075E 2400N	92
5075E 2425N	44
5075E 2450N	10
5075E 2475N	80
5075E 2500N	24
5075E 2525N	N. S.
5075E 2550N	86
*0211	2268
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3613-SG3

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment32**
Attn: **Sue Deane**

Oct-21-08

We *hereby certify* the following geochemical analysis of 22 soil samples submitted Oct-06-08

Sample Name	Au ppb
5075E 2575N	6
5075E 2600N	144
5075E 2625N	642
5075E 2650N	140
5075E 2675N	2640
5075E 2700N	62
5075E 2725N	24
5075E 2750N	38
5075E 2775N	174
5075E 2800N	222
5100E 2300N	2230
5100E 2325N	84
5100E 2350N	10
5100E 2375N	<1
5100E 2400N	26
5100E 2425N	4
5100E 2450N	664
5100E 2475N	164
5100E 2500N	6
5100E 2525N	20
5100E 2550N N.S.	
5100E 2575N	110
*0211	2190
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3613-SG4

Company: **Ascot Resources Ltd**
Project: Dilworth/shipment32
Attn: Sue Deane

Oct-21-08

We *hereby certify* the following geochemical analysis of 22 soil samples submitted Oct-06-08

Sample Name	Au ppb
5100E 2600N	1036
5100E 2625N	22
5100E 2650N	130
5100E 2675N	102
5100E 2700N	94
5100E 2725N	202
5100E 2750N	52
5100E 2775N	350
5100E 2800N	146
5125E 2300N	100
5125E 2325N	32
5125E 2350N	24
5125E 2375N	<1
5125E 2400N	1814
5125E 2425N	118
5125E 2450N	14
5125E 2475N	236
5125E 2500N	230
5125E 2525N	126
5125E 2550N	15
5125E 2575N	216
5125E 2600N	74
*0211	2151
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3613-SG5

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment32**
Attn: **Sue Deane**

Oct-21-08

We *hereby certify* the following geochemical analysis of 22 soil samples submitted Oct-06-08

Sample Name	Au ppb
5125E 2625N N.S.	393
5125E 2650N	636
5125E 2675N	16
5125E 2700N	1418
5125E 2725N	82
5125E 2750N	68
5125E 2775N	44
5125E 2800N	8
5150E 2300N	16
5150E 2325N	44
5150E 2350N	48
5150E 2375N	26
5150E 2400N	48
5150E 2425N	148
5150E 2450N	478
5150E 2475N	66
5150E 2500N	14
5150E 2525N	14
5150E 2550N	
5150E 2575N N.S.	
5150E 2600N N.S.	312
5150E 2625N	2192
*0211	<1
*BLANK	

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3613-SG6

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment32**
Attn: **Sue Deane**

Oct-21-08

We *hereby certify* the following geochemical analysis of 22 soil samples submitted Oct-06-08

Sample Name	Au ppb
5150E 2650N	1275
5150E 2675N	214
5150E 2700N	38
5150E 2725N	68
5150E 2750N	592
5150E 2775N	214
5150E 2800N	94
5175E 2300N	52
5175E 2325N	18
5175E 2350N	21
5175E 2375N	12
5175E 2400N	26
5175E 2425N	26
5175E 2450N	118
5175E 2475N	44
5175E 2500N	142
5175E 2525N	6
5175E 2550N	88
5175E 2575N	2642
5175E 2600N	300
5175E 2625N N.S.	
5175E 2650N	1860
*0211	2241
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3613-SG7

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment32**
Attn: **Sue Deane**

Oct-21-08

We *hereby certify* the following geochemical analysis of 22 soil samples submitted Oct-06-08

Sample Name	Au ppb
5175E 2675N	1984
5175E 2700N	122
5175E 2725N	9
5175E 2750N	42
5175E 2775N	269
5175E 2800N	171
5200E 2300N	41
5200E 2325N	39
5200E 2350N	12
5200E 2375N	20
5200E 2400N	2954
5200E 2425N	128
5200E 2450N	18
5200E 2475N	30
5200E 2500N N.S.	
5200E 2525N	18
5200E 2550N	288
5200E 2575N	1505
5200E 2600N	602
5200E 2625N	291
5200E 2650N	624
5200E 2675N	50
*0211	2145
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3613-SG8

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment32**
Attn: **Sue Deane**

Oct-21-08

We *hereby certify* the following geochemical analysis of 22 soil samples submitted Oct-06-08

Sample Name	Au ppb
5200E 2700N	1410
5200E 2725N	208
5200E 2750N	62
5200E 2775N	784
5200E 2800N	402
5225E 2300N	55
5225E 2325N	284
5225E 2350N	2
5225E 2375N	12
5225E 2400N	852
5225E 2425N	12
5225E 2450N	48
5225E 2475N	60
5225E 2500N	206
5225E 2525N	2253
5225E 2550N	171
5225E 2575N	122
5225E 2600N	560
5225E 2625N	495
5225E 2650N	1203
5225E 2675N	1011
5225E 2700N	59
*0211	2210
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3613-SG9

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment32**
Attn: **Sue Deane**

Oct-21-08

We hereby certify the following geochemical analysis of 22 soil samples submitted Oct-06-08

Sample Name	Au ppb
5225E 2725N	74
5225E 2750N	105
5225E 2775N	69
5225E 2800N	242
5250E 2300N	12
5250E 2325N	47
5250E 2350N	<1
5250E 2375N	12
5250E 2400N	14
5250E 2425N	5
5250E 2450N	8
5250E 2475N	<1
5250E 2500N	3
5250E 2525N	377
5250E 2550N	510
5250E 2575N	27
5250E 2600N	20
5250E 2625N	266
5250E 2650N	1299
5250E 2675N	251
5250E 2700N	66
5250E 2725N	772
*0211	2221
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3613-SG10

Company: **Ascot Resources Ltd**
Project: Dilworth/shipment32
Attn: Sue Deane

Oct-21-08

We *hereby certify* the following geochemical analysis of 22 soil samples submitted Oct-06-08

Sample Name	Au ppb
5250E 2750N	1287
5250E 2775N	113
5250E 2800N	588
5275E 2300N	996
5275E 2325N	57
5275E 2350N	549
5275E 2375N	14
5275E 2400N	18
5275E 2425N	5
5275E 2450N	14
5275E 2475N	36
5275E 2500N	47
5275E 2525N	615
5275E 2550N	701
5275E 2575N	189
5275E 2600N	702
5275E 2625N	293
5275E 2650N	494
5275E 2675N	128
5275E 2700N	38
5275E 2725N	2160
5275E 2750N	1419
*0211	2076
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3613-SG11

Company: **Ascot Resources Ltd**
Project: Dilworth/shipment32
Attn: Sue Deane

Oct-21-08

We hereby certify the following geochemical analysis of 22 soil samples submitted Oct-06-08

Sample Name	Au ppb
5275E 2775N	30
5275E 2800N	1956
5300E 2300N	50
5300E 2325N	84
5300E 2350N	19
5300E 2375N	24
5300E 2400N	29
5300E 2425N	6
5300E 2450N	20
5300E 2475N	12
5300E 2500N	19
5300E 2525N	756
5300E 2550N	546
5300E 2575N	64
5300E 2600N	47
5300E 2625N	298
5300E 2650N	8
5300E 2675N	64
5300E 2700N	1710
5300E 2725N	<1
5300E 2750N	528
5300E 2775N	128
*0211	2106
*BLANK	<1

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Geochemical Analysis Certificate

8V-3613-SG12

Company: **Ascot Resources Ltd**
Project: Dilworth/shipment32
Attn: Sue Deane

Oct-21-08

We *hereby certify* the following geochemical analysis of 1 soil sample submitted Oct-06-08

Sample Name	Au ppb
5300E 2800N	1161
*0211	2187
*BLANK	<1

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3613SJ

Date : Oct-21-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment32

Sample type: Soil

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
5000E 2550N	<0.2	1.28	111	72	<0.5	<5	0.06	3	11	29	19	5.15	<1	0.06	15	0.21	1007	3	<0.01	1	1500	55	0.04	11	2	8	<5	0.13	<10	<10	207	<10	50	4
5000E 2575N	<0.2	1.50	102	46	<0.5	<5	0.05	2	9	20	18	5.06	<1	0.07	11	0.26	1440	4	<0.01	1	2172	53	0.06	10	1	8	<5	0.08	<10	<10	164	<10	41	4
5000E 2600N	<0.2	0.62	5	19	<0.5	<5	0.02	2	1	6	4	0.33	<1	0.05	<10	0.03	75	<2	<0.01	<1	687	18	0.04	<5	<1	3	<5	0.01	<10	13	13	<10	7	1
5000E 2625N	2.5	1.09	212	53	<0.5	<5	0.02	6	14	15	39	3.64	<1	0.07	10	0.08	221	2	<0.01	2	829	61	0.04	11	2	4	<5	0.01	<10	<10	186	<10	78	3
5000E 2650N	<0.2	2.19	298	203	0.5	<5	0.01	8	26	<1	105	10.04	<1	0.07	24	0.10	>10000	<2	<0.01	<1	1448	166	0.07	23	12	5	<5	<0.01	<10	<10	188	<10	111	13
5000E 2675N	<0.2	2.11	113	70	<0.5	<5	0.03	2	7	19	18	6.10	<1	0.04	<10	0.28	564	2	<0.01	<1	978	58	0.03	13	2	7	<5	0.01	<10	<10	154	<10	59	5
5000E 2700N	<0.2	0.88	13	59	<0.5	<5	0.05	<1	3	13	5	1.12	<1	0.04	11	0.06	75	2	<0.01	2	366	30	0.03	<5	1	7	<5	0.06	<10	<10	59	<10	15	1
5000E 2725N	<0.2	1.75	102	108	<0.5	<5	0.05	2	11	32	19	6.65	<1	0.05	<10	0.35	260	2	<0.01	<1	1135	45	0.12	15	5	5	<5	0.15	<10	<10	378	<10	27	5
5000E 2750N	<0.2	1.58	97	113	<0.5	<5	0.16	2	19	22	28	4.95	<1	0.07	17	0.74	1615	2	<0.01	20	1378	63	0.04	11	2	9	<5	0.01	<10	13	95	<10	115	4
5000E 2775N	<0.2	2.65	26	28	<0.5	<5	0.02	<1	7	35	1	9.36	<1	0.05	19	0.09	449	7	<0.01	<1	974	51	0.08	18	2	5	<5	0.24	<10	61	169	<10	50	45
5000E 2800N	<0.2	2.20	37	133	<0.5	<5	0.17	1	18	29	26	7.17	<1	0.07	10	0.43	1751	2	0.01	<1	2313	81	0.06	14	3	6	<5	0.03	<10	<10	316	<10	62	6
5025E 2550N	11.7	3.14	978	100	<0.5	<5	0.18	28	48	107	92	7.65	<1	0.11	10	1.35	5369	<2	<0.01	5	2180	3691	0.07	38	13	7	<5	0.01	<10	<10	351	<10	307	6
5025E 2575N	<0.2	1.59	21	58	<0.5	<5	0.01	<1	5	7	7	3.00	<1	0.07	16	0.10	290	<2	<0.01	<1	1108	54	0.02	6	2	4	<5	0.01	<10	15	67	<10	58	3
5025E 2600N	<0.2	1.94	317	78	<0.5	<5	0.10	8	37	<1	60	7.21	<1	0.14	17	0.34	>10000	2	<0.01	<1	5509	760	0.09	18	2	8	<5	0.02	<10	<10	169	<10	162	6
5025E 2625N	<0.2	2.04	59	42	<0.5	<5	0.54	1	11	31	11	7.13	<1	0.05	<10	0.41	482	3	<0.01	6	784	56	0.05	15	2	14	<5	0.19	<10	<10	191	<10	51	8
5025E 2650N	<0.2	2.36	64	61	<0.5	<5	0.24	1	15	2	28	10.10	<1	0.08	12	0.23	2807	<2	<0.01	<1	2618	64	0.05	17	1	7	<5	0.02	<10	<10	251	<10	62	8
5025E 2675N	<0.2	2.01	23	35	<0.5	<5	0.09	<1	7	24	11	3.81	<1	0.05	<10	0.39	391	2	<0.01	5	932	45	0.06	9	1	13	<5	0.11	<10	<10	118	<10	41	4
5025E 2700N	<0.2	2.07	58	117	<0.5	<5	0.05	1	10	<1	20	4.00	<1	0.11	16	0.29	2328	<2	<0.01	<1	2866	51	0.03	9	2	7	<5	0.01	<10	<10	128	<10	55	3
5025E 2725N	<0.2	2.11	45	55	<0.5	<5	0.06	<1	10	40	13	8.02	<1	0.05	<10	0.47	427	2	<0.01	7	842	43	0.04	16	2	12	<5	0.17	<10	<10	212	<10	53	12
5025E 2750N	<0.2	3.21	105	79	<0.5	<5	0.05	2	15	69	34	7.26	<1	0.06	<10	0.73	628	3	<0.01	31	878	58	0.07	17	7	9	<5	0.09	<10	<10	205	<10	100	15
5025E 2775N	<0.2	3.69	63	75	<0.5	<5	0.32	2	14	3	34	6.75	<1	0.07	<10	0.25	2168	2	<0.01	<1	1594	106	0.10	14	2	7	<5	0.06	<10	<10	164	<10	58	5
5025E 2800N	<0.2	2.26	198	60	<0.5	<5	0.02	5	22	32	41	8.17	<1	0.07	14	0.38	1951	4	<0.01	12	1148	114	0.06	17	2	6	<5	0.13	<10	<10	175	<10	93	9
5050E 2550N	<0.2	2.05	122	51	<0.5	<5	0.04	1	19	62	43	9.50	<1	0.06	15	0.25	909	4	0.01	4	1219	56	0.04	20	8	6	<5	0.15	<10	<10	306	<10	105	12
5050E 2575N	<0.2	1.18	47	28	<0.5	<5	0.02	<1	8	20	9	4.82	<1	0.07	17	0.11	282	4	<0.01	1	908	41	0.05	9	1	5	<5	0.17	<10	<10	129	<10	61	15
5050E 2600N	<0.2	1.61	99	144	<0.5	<5	0.15	2	40	<1	54	7.77	<1	0.12	<10	0.58	4154	2	0.02	1	4383	97	0.10	14	6	8	<5	0.01	<10	<10	244	<10	159	6
5050E 2625N	<0.2	0.79	162	97	<0.5	<5	0.09	3	34	<1	39	6.69	<1	0.12	<10	0.20	7159	<2	<0.01	<1	4305	64	0.06	13	3	5	<5	0.01	<10	<10	173	<10	81	5
5050E 2650N	<0.2	1.38	221	73	<0.5	<5	0.03	4	10	<1	6	6.84	<1	0.09	11	0.11	1509	2	0.04	<1	1248	96	0.04	12	1	4	<5	0.02	<10	<10	155	<10	96	5
5050E 2675N	<0.2	1.43	42	42	<0.5	<5	0.05	<1	6	25	6	4.55	<1	0.05	11	0.14	185	2	<0.01	<1	1249	38	0.03	9	2	9	<5	0.11	<10	<10	206	<10	27	4
5050E 2700N	<0.2	3.03	493	98	<0.5	<5	0.01	9	31	<1	61	9.83	<1	0.09	14	0.38	3069	<2	0.01	<1	2473	93	0.08	21	4	4	<5	0.01	<10	<10	262	<10	86	8
5050E 2725N	<0.2	1.92	131	57	<0.5	<5	0.05	2	7	25	27	4.54	<1	0.10	11	0.42	611	2	<0.01	4	2019	115	0.08	10	1	6	<5	0.01	<10	<10	117	<10	75	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3613SJ

Date : Oct-21-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment32

Sample type: Soil

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
5050E 2750N	<0.2	2.51	83	149	<0.5	<5	0.10	1	11	9	27	9.20	<1	0.09	<10	0.31	751	<2	<0.01	<1	1589	75	0.08	17	3	10	<5	0.06	<10	<10	313	<10	49	6
5050E 2775N	<0.2	2.70	220	82	<0.5	<5	0.03	4	12	<1	22	8.67	<1	0.10	11	0.48	2031	<2	0.01	<1	2805	64	0.07	17	3	6	<5	0.03	<10	<10	248	<10	80	7
5050E 2800N	<0.2	1.05	199	105	<0.5	<5	0.02	4	14	<1	16	3.51	<1	0.08	13	0.09	3306	<2	<0.01	<1	1188	138	0.04	7	<1	5	<5	0.05	<10	<10	137	<10	64	2
5075E 2300N	<0.2	3.56	147	56	<0.5	<5	0.05	2	14	<1	25	6.51	<1	0.07	11	0.36	1188	<2	<0.01	<1	1031	48	0.09	18	2	4	<5	0.15	<10	<10	173	<10	59	5
5075E 2325N	<0.2	1.83	258	68	<0.5	<5	0.11	5	24	<1	22	8.78	<1	0.10	<10	0.21	2391	2	<0.01	<1	2528	134	0.10	18	1	7	<5	0.18	<10	<10	302	<10	54	6
5075E 2350N	<0.2	1.38	69	44	<0.5	<5	0.08	1	23	26	6	5.71	<1	0.06	10	0.18	1734	9	<0.01	2	915	49	0.07	12	2	8	<5	0.24	<10	<10	283	<10	34	8
5075E 2375N	<0.2	1.71	176	97	<0.5	<5	0.07	3	14	<1	17	6.53	<1	0.12	<10	0.20	2241	2	<0.01	<1	1074	155	0.09	12	1	6	<5	0.08	<10	<10	244	<10	53	4
5075E 2400N	<0.2	1.74	121	366	<0.5	<5	0.64	3	17	<1	12	4.22	<1	0.10	10	0.36	5562	2	0.02	11	2059	212	0.11	9	<1	23	<5	0.02	<10	<10	139	<10	112	3
5075E 2425N	<0.2	1.41	72	53	0.5	<5	0.09	1	15	<1	15	3.79	<1	0.12	<10	0.45	2227	2	0.01	<1	1133	75	0.07	6	1	5	<5	0.01	<10	<10	99	<10	96	3
5075E 2450N	<0.2	2.19	138	81	<0.5	<5	0.09	3	17	53	18	5.74	<1	0.13	13	0.51	1308	<2	0.04	<1	1990	78	0.11	12	2	6	<5	0.01	<10	<10	177	<10	91	5
5075E 2475N	<0.2	0.97	140	74	<0.5	<5	0.12	3	7	17	17	3.49	<1	0.09	<10	0.30	377	<2	0.04	2	906	30	0.09	7	1	11	<5	0.03	<10	<10	89	<10	77	2
5075E 2500N	<0.2	2.41	165	95	<0.5	<5	0.02	2	15	29	28	8.25	<1	0.08	11	0.27	1087	<2	0.02	<1	1153	63	0.04	16	6	4	<5	0.01	<10	<10	256	<10	76	6
5075E 2550N	<0.2	2.02	216	91	<0.5	<5	0.02	3	12	33	38	9.30	<1	0.07	14	0.20	729	<2	0.03	<1	2209	61	0.05	18	7	5	<5	0.02	<10	<10	301	<10	99	6
5075E 2575N	<0.2	0.69	14	18	<0.5	<5	0.01	<1	3	5	5	1.12	<1	0.07	10	0.04	271	3	<0.01	1	733	16	0.03	<5	1	3	<5	0.01	<10	11	28	<10	30	2
5075E 2600N	<0.2	1.06	109	39	<0.5	<5	0.07	2	5	23	23	3.02	<1	0.13	13	0.30	502	<2	<0.01	3	1494	75	0.05	6	1	5	<5	0.01	<10	11	82	<10	50	2
5075E 2625N	<0.2	1.24	86	240	<0.5	<5	0.20	1	31	24	37	7.04	<1	0.11	<10	0.17	3327	2	0.04	2	1995	98	0.06	13	9	11	<5	<0.01	<10	<10	212	<10	81	5
5075E 2650N	<0.2	1.05	129	77	0.5	<5	0.02	2	24	<1	60	7.29	<1	0.13	12	0.09	2101	2	0.01	<1	2386	101	0.04	13	3	3	<5	<0.01	<10	<10	157	<10	118	5
5075E 2675N	17.9	2.63	9416	116	2.4	<5	0.06	201	71	<1	190	>15.00	<1	0.10	21	0.30	8398	<2	0.02	<1	3382	508	0.10	55	9	7	<5	0.01	<10	25	353	<10	348	20
5075E 2700N	<0.2	1.56	68	36	<0.5	<5	0.02	1	8	3	68	5.18	<1	0.07	15	0.09	638	3	0.05	<1	961	23	0.03	9	3	5	<5	<0.01	<10	<10	224	<10	104	4
5075E 2725N	<0.2	2.35	665	82	<0.5	<5	0.02	13	14	22	16	10.16	<1	0.08	14	0.20	1496	2	0.04	<1	1980	97	0.06	19	2	5	<5	0.09	<10	<10	323	<10	73	7
5075E 2750N	<0.2	1.36	112	62	<0.5	<5	0.05	2	14	<1	11	7.59	<1	0.08	12	0.23	3147	2	0.03	<1	3127	156	0.05	14	1	10	<5	0.10	<10	<10	210	<10	88	5
5075E 2775N	<0.2	2.13	235	129	<0.5	<5	0.04	5	15	24	25	7.12	<1	0.07	11	0.32	1688	4	0.01	2	3403	83	0.07	16	2	6	<5	0.01	<10	<10	157	<10	128	7
5075E 2800N	<0.2	1.80	159	64	<0.5	<5	0.05	3	10	18	36	6.06	<1	0.07	13	0.24	369	<2	<0.01	<1	1727	47	0.06	12	3	9	<5	0.01	<10	<10	228	<10	35	5
5100E 2300N	<0.2	1.80	2780	70	<0.5	<5	0.04	56	46	<1	59	8.50	<1	0.15	12	0.52	4861	2	0.01	<1	2925	151	0.05	30	2	5	<5	0.06	<10	<10	176	<10	122	6
5100E 2325N	<0.2	2.49	90	58	<0.5	<5	0.23	1	14	57	17	5.21	<1	0.04	10	0.63	931	<2	0.02	12	1241	50	0.06	12	2	13	<5	0.13	<10	<10	167	<10	89	9
5100E 2350N	<0.2	0.98	31	20	<0.5	<5	0.02	<1	7	21	4	2.73	<1	0.04	11	0.07	162	3	<0.01	<1	477	44	0.05	7	<1	3	<5	0.27	<10	15	114	<10	40	25
5100E 2375N	<0.2	1.21	26	53	<0.5	<5	0.02	<1	5	30	4	2.30	<1	0.05	16	0.08	149	2	<0.01	2	710	43	0.05	5	1	5	<5	0.06	<10	<10	113	<10	34	3
5100E 2400N	<0.2	1.12	79	34	<0.5	<5	0.03	1	11	2	24	2.83	<1	0.10	10	0.18	509	<2	<0.01	<1	994	29	0.05	6	1	3	<5	0.01	<10	<10	121	<10	29	2
5100E 2425N	<0.2	0.80	9	28	<0.5	<5	0.05	<1	2	5	5	0.64	<1	0.08	<10	0.06	180	<2	<0.01	1	863	23	0.08	<5	<1	3	<5	0.02	<10	<10	23	<10	18	2
5100E 2450N	<0.2	1.80	2750	109	0.8	<5	0.01	53	52	<1	98	10.49	<1	0.12	18	0.33	6891	<2	0.01	<1	2418	163	0.08	33	5	4	<5	<0.01	<10	<10	208	<10	230	9

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3613SJ

Date : Oct-21-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment32

Sample type: Soil

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
5100E 2475N	<0.2	2.22	652	153	0.7	<5	0.99	15	55	<1	117	9.29	<1	0.16	18	0.75	8080	4	<0.01	<1	3767	173	0.30	21	7	28	<5	0.01	<10	<10	236	<10	284	7
5100E 2500N	<0.2	2.55	47	92	<0.5	<5	0.04	1	7	13	16	5.65	<1	0.06	10	0.21	669	<2	<0.01	<1	963	50	0.05	11	2	4	<5	0.02	<10	<10	225	<10	38	5
5100E 2525N	<0.2	1.51	71	51	<0.5	<5	0.05	1	8	42	10	4.29	<1	0.05	11	0.69	435	2	0.03	13	771	39	0.04	9	2	5	<5	0.02	<10	<10	126	<10	73	5
5100E 2575N	<0.2	2.04	340	148	0.6	<5	0.15	6	84	<1	79	8.85	<1	0.10	16	0.72	4950	2	0.03	<1	2475	112	0.14	20	7	9	<5	0.01	<10	<10	220	<10	138	7
5100E 2600N	<0.2	1.36	285	234	<0.5	<5	0.05	5	67	<1	63	9.39	<1	0.12	12	0.15	>10000	2	0.02	<1	6053	131	0.10	18	4	7	<5	0.01	<10	<10	231	<10	139	7
5100E 2625N	<0.2	1.46	67	47	<0.5	<5	0.11	1	6	5	18	2.82	<1	0.08	<10	0.16	409	<2	<0.01	<1	1477	25	0.07	6	2	5	<5	0.01	<10	<10	149	<10	52	2
5100E 2650N	<0.2	1.92	86	60	<0.5	<5	0.05	1	9	46	17	6.95	<1	0.04	10	0.30	695	<2	<0.01	4	1435	57	0.06	14	2	8	<5	0.10	<10	<10	293	<10	58	5
5100E 2675N	6.9	1.57	43	44	<0.5	<5	0.05	1	3	28	15	2.29	<1	0.10	10	0.18	188	2	<0.01	2	1922	60	0.10	<5	<1	5	<5	0.01	<10	<10	93	<10	39	2
5100E 2700N	<0.2	1.22	123	77	<0.5	<5	0.04	2	8	15	31	4.46	<1	0.06	11	0.10	388	4	0.02	<1	872	65	0.04	10	1	6	<5	0.07	<10	<10	174	<10	76	3
5100E 2725N	<0.2	1.24	834	67	<0.5	<5	0.01	17	19	14	49	8.28	<1	0.06	<10	0.08	711	12	<0.01	<1	1671	653	0.07	21	2	5	<5	0.03	<10	<10	218	13	952	5
5100E 2750N	<0.2	1.09	62	121	<0.5	<5	0.06	1	5	18	13	3.94	<1	0.08	14	0.08	247	4	<0.01	<1	989	39	0.04	8	1	6	<5	0.05	<10	<10	192	<10	61	3
5100E 2775N	<0.2	1.18	103	70	<0.5	<5	0.06	2	9	33	14	4.05	<1	0.05	10	0.34	835	3	0.01	4	1630	61	0.04	9	1	6	<5	0.02	<10	<10	124	<10	56	4
5100E 2800N	1.0	0.87	87	96	<0.5	<5	0.10	2	5	22	11	3.25	<1	0.06	<10	0.25	217	2	<0.01	<1	1251	44	0.05	7	1	7	<5	0.01	<10	<10	81	<10	51	3
5125E 2300N	<0.2	2.19	834	75	<0.5	<5	0.08	17	32	<1	24	7.17	<1	0.11	10	0.40	3996	3	0.02	<1	1553	106	0.14	18	1	7	<5	0.13	<10	<10	225	<10	136	5
5125E 2325N	<0.2	2.33	36	49	<0.5	<5	0.13	<1	10	94	5	4.93	<1	0.07	12	0.45	182	6	<0.01	9	1001	92	0.09	12	2	6	<5	0.20	<10	<10	184	<10	62	16
5125E 2350N	<0.2	1.06	162	70	<0.5	<5	0.07	3	11	<1	9	4.20	<1	0.12	10	0.19	3313	5	<0.01	<1	1911	97	0.09	8	<1	5	<5	0.02	<10	<10	118	<10	63	3
5125E 2375N	1.0	0.44	8	29	<0.5	<5	0.06	<1	1	7	4	0.50	<1	0.07	<10	0.03	82	<2	<0.01	1	1068	18	0.06	<5	<1	4	<5	0.01	<10	<10	16	<10	19	1
5125E 2400N	<0.2	2.67	2034	85	<0.5	<5	0.06	44	29	<1	37	7.71	<1	0.07	<10	0.11	>10000	13	0.04	<1	2255	423	0.15	23	1	5	<5	0.03	<10	<10	192	<10	127	29
5125E 2425N	<0.2	1.97	134	61	<0.5	<5	0.10	3	8	65	63	3.59	<1	0.08	14	0.41	330	3	0.01	12	1391	83	0.09	10	2	7	<5	0.13	<10	13	126	<10	87	10
5125E 2450N	<0.2	1.75	71	61	<0.5	<5	0.05	1	10	36	14	6.22	<1	0.05	<10	0.17	605	3	<0.01	2	890	46	0.07	13	2	7	<5	0.12	<10	<10	251	<10	65	5
5125E 2475N	<0.2	1.69	929	69	<0.5	<5	0.05	19	11	51	20	7.16	<1	0.05	11	0.26	930	<2	0.01	4	1044	67	0.06	17	2	7	<5	0.09	<10	<10	246	<10	95	5
5125E 2500N	1.3	1.08	449	70	<0.5	<5	0.03	9	8	<1	14	4.29	<1	0.08	<10	0.13	1104	<2	<0.01	<1	1342	51	0.05	9	1	4	<5	0.02	<10	<10	154	<10	29	3
5125E 2525N	<0.2	1.28	73	51	<0.5	<5	0.04	1	9	43	10	4.31	<1	0.04	<10	0.48	750	2	<0.01	11	997	44	0.05	8	2	4	<5	0.01	<10	<10	117	<10	71	4
5125E 2550N	<0.2	0.64	20	15	<0.5	<5	0.01	<1	3	6	5	1.02	<1	0.05	<10	0.02	81	<2	<0.01	1	400	13	0.02	<5	1	2	<5	0.01	<10	13	37	<10	29	2
5125E 2575N	<0.2	1.52	931	73	<0.5	<5	0.03	19	12	22	25	7.10	<1	0.08	<10	0.14	484	2	<0.01	<1	1046	78	0.05	16	2	5	<5	0.01	<10	<10	223	<10	64	5
5125E 2600N	<0.2	1.44	123	77	<0.5	<5	0.13	2	5	8	15	5.20	<1	0.06	<10	0.21	389	16	<0.01	<1	1415	41	0.08	12	1	6	<5	0.01	<10	<10	163	<10	60	5
5125E 2650N	<0.2	0.99	760	275	<0.5	<5	0.05	20	14	<1	11	7.90	<1	0.08	<10	0.07	6792	9	<0.01	<1	1035	97	0.36	19	3	4	<5	<0.01	<10	<10	120	<10	61	6
5125E 2675N	<0.2	2.29	640	68	<0.5	<5	0.04	17	18	<1	43	6.01	<1	0.15	14	0.34	3073	5	<0.01	<1	3907	173	0.06	14	4	4	<5	0.01	<10	14	139	<10	101	10
5125E 2700N	<0.2	1.28	41	43	<0.5	<5	0.04	1	6	19	9	4.08	<1	0.06	11	0.12	431	2	<0.01	2	938	64	0.04	9	1	7	<5	0.09	<10	<10	132	<10	57	4
5125E 2725N	90.3	1.00	1327	92	<0.5	<5	0.07	36	11	10	84	6.96	<1	0.08	<10	0.13	260	12	<0.01	1	3514	2192	0.16	33	2	9	<5	0.03	<10	<10	216	<10	383	5

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3613SJ

Date : Oct-21-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment32

Sample type: Soil

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
5125E 2750N	<0.2	2.37	53	70	<0.5	<5	0.03	1	5	9	16	4.92	<1	0.06	11	0.11	641	2	<0.01	<1	2593	54	0.06	10	1	6	<5	0.02	<10	<10	152	<10	31	5
5125E 2775N	<0.2	2.70	55	107	<0.5	<5	0.06	1	5	14	13	6.62	<1	0.05	<10	0.18	531	2	<0.01	<1	1294	69	0.08	13	1	8	<5	0.05	<10	<10	151	<10	34	5
5125E 2800N	<0.2	1.76	58	133	<0.5	<5	0.05	1	7	8	25	4.87	<1	0.05	<10	0.17	172	<2	<0.01	<1	1078	40	0.05	11	3	12	<5	0.04	<10	<10	240	<10	27	4
5150E 2300N	<0.2	2.15	35	62	<0.5	<5	0.05	1	7	10	13	2.90	<1	0.08	<10	0.32	743	<2	<0.01	1	1225	34	0.07	7	1	6	<5	0.04	<10	<10	100	<10	39	2
5150E 2325N	<0.2	2.29	65	46	<0.5	<5	0.19	1	9	33	15	3.55	<1	0.07	13	0.56	351	3	<0.01	13	1387	60	0.08	9	1	11	<5	0.10	<10	19	97	<10	89	7
5150E 2350N	<0.2	3.04	803	99	<0.5	<5	0.35	22	28	24	45	5.82	<1	0.07	15	0.80	2279	2	<0.01	23	1954	82	0.06	14	3	21	<5	0.09	<10	32	135	<10	276	7
5150E 2375N	<0.2	3.77	208	42	<0.5	<5	0.06	6	18	16	26	3.74	<1	0.05	25	0.19	1224	2	0.03	1	2227	104	0.15	10	1	5	<5	0.04	<10	64	79	<10	99	5
5150E 2400N	<0.2	1.78	73	76	<0.5	<5	0.13	2	7	3	11	1.65	<1	0.08	10	0.13	417	2	<0.01	<1	780	33	0.04	6	1	5	<5	0.01	<10	<10	82	<10	23	2
5150E 2425N	<0.2	3.84	224	90	<0.5	<5	0.32	6	60	<1	57	7.12	<1	0.16	14	0.87	6421	4	0.03	<1	2512	168	0.10	18	3	13	<5	0.10	<10	<10	176	<10	204	7
5150E 2450N	<0.2	3.91	524	91	<0.5	<5	0.20	14	65	<1	158	9.17	<1	0.15	18	1.07	4817	6	<0.01	3	3068	341	0.08	21	7	10	<5	0.11	<10	28	220	<10	355	16
5150E 2475N	0.3	1.97	365	78	<0.5	<5	0.12	10	23	<1	54	5.72	<1	0.13	21	0.40	3873	<2	<0.01	<1	2256	196	0.09	13	4	6	<5	0.01	<10	<10	126	<10	154	5
5150E 2500N	<0.2	3.53	240	65	<0.5	<5	0.04	6	55	<1	37	9.42	<1	0.10	12	0.43	6365	<2	<0.01	<1	2274	224	0.09	22	2	6	<5	0.05	<10	<10	208	<10	160	8
5150E 2525N	<0.2	0.89	67	43	<0.5	<5	0.06	2	12	20	16	4.25	<1	0.06	<10	0.44	481	<2	<0.01	9	1327	49	0.07	9	2	5	<5	0.01	<10	<10	83	<10	87	4
5150E 2550N	<0.2	1.17	49	92	<0.5	<5	0.30	1	17	24	20	4.61	<1	0.05	13	0.71	947	<2	<0.01	19	1523	42	0.05	9	4	12	<5	0.01	<10	13	89	<10	119	4
5150E 2625N	3.2	1.55	515	73	<0.5	<5	0.14	13	18	10	79	6.41	<1	0.11	16	0.59	1673	3	<0.01	1	2107	215	0.09	17	3	8	<5	0.02	<10	18	132	<10	136	6
5150E 2650N	<0.2	0.58	4046	398	0.6	<5	0.11	110	15	<1	56	9.04	<1	0.12	<10	0.07	5158	2	<0.01	<1	1504	505	0.21	38	2	9	<5	<0.01	<10	<10	128	<10	139	7
5150E 2675N	<0.2	1.17	59	46	<0.5	<5	0.03	1	3	6	7	2.04	<1	0.09	11	0.06	493	3	<0.01	<1	895	45	0.06	5	1	4	<5	0.05	<10	14	58	<10	27	4
5150E 2700N	<0.2	1.81	37	33	<0.5	<5	0.07	<1	11	34	9	5.98	<1	0.04	<10	0.42	472	2	<0.01	7	593	63	0.04	13	2	12	<5	0.18	<10	<10	173	<10	63	9
5150E 2725N	<0.2	2.31	48	53	<0.5	<5	0.26	1	12	42	20	5.49	<1	0.04	<10	0.79	483	<2	<0.01	17	1273	95	0.03	12	4	16	<5	0.13	<10	<10	145	<10	113	6
5150E 2750N	<0.2	1.89	560	78	<0.5	<5	0.03	15	20	<1	30	5.64	<1	0.12	11	0.24	5716	2	<0.01	<1	2179	102	0.06	15	1	6	<5	0.02	<10	<10	123	<10	56	5
5150E 2775N	<0.2	1.19	65	76	<0.5	<5	0.02	1	5	17	11	3.12	<1	0.07	11	0.17	537	2	<0.01	2	1322	40	0.03	7	1	5	<5	0.01	<10	10	74	<10	32	3
5150E 2800N	<0.2	1.43	107	58	<0.5	<5	0.06	2	7	13	15	4.84	<1	0.05	10	0.18	381	4	<0.01	<1	975	43	0.02	12	2	12	<5	0.06	<10	<10	150	<10	56	4
5175E 2300N	<0.2	1.86	434	126	<0.5	<5	0.56	12	10	28	11	4.62	<1	0.05	<10	0.39	500	2	<0.01	7	1212	62	0.10	10	2	29	<5	0.11	<10	<10	121	<10	78	4
5175E 2325N	<0.2	0.68	26	54	<0.5	<5	0.09	1	5	6	12	1.77	<1	0.07	<10	0.08	222	<2	<0.01	<1	641	21	0.04	<5	1	8	<5	0.04	<10	<10	70	<10	20	1
5175E 2350N	<0.2	1.11	96	49	<0.5	<5	0.06	2	11	5	11	3.94	<1	0.11	<10	0.19	1287	2	<0.01	<1	1198	41	0.07	10	1	5	<5	0.12	<10	<10	136	<10	30	4
5175E 2375N	<0.2	1.48	17	18	<0.5	<5	0.03	<1	4	20	5	2.41	<1	0.05	<10	0.07	96	2	<0.01	<1	753	35	0.06	7	1	4	<5	0.07	<10	<10	63	<10	27	3
5175E 2400N	<0.2	5.31	661	71	1.6	<5	0.77	18	25	23	24	4.42	<1	0.05	19	0.42	2006	2	<0.01	10	1756	92	0.10	14	3	28	<5	0.08	<10	51	103	<10	192	13
5175E 2425N	<0.2	2.35	178	57	<0.5	<5	0.23	4	10	17	14	6.44	<1	0.09	20	0.25	1505	16	0.02	<1	1323	101	0.13	14	2	9	<5	0.15	<10	59	152	<10	154	12
5175E 2450N	<0.2	2.63	184	94	<0.5	<5	0.32	5	19	19	43	4.58	<1	0.10	17	0.65	1845	4	0.01	16	1801	83	0.06	11	3	15	<5	0.08	<10	26	107	<10	168	6
5175E 2475N	<0.2	1.50	193	82	<0.5	<5	0.52	5	16	<1	13	5.03	<1	0.11	<10	0.16	1628	2	<0.01	<1	1117	175	0.05	12	1	6	<5	0.12	<10	<10	193	<10	44	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3613SJ

Date : Oct-21-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment32

Sample type: Soil

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
5175E 2500N	<0.2	2.46	299	99	<0.5	<5	0.36	10	29	1	65	7.01	<1	0.16	15	1.21	2827	<2	<0.01	7	2291	224	0.07	17	4	12	<5	0.08	<10	21	151	<10	430	9
5175E 2525N	<0.2	1.08	16	93	<0.5	<5	0.33	<1	15	35	18	4.29	<1	0.05	11	0.70	624	<2	<0.01	32	1341	28	0.10	8	4	16	<5	0.01	<10	13	85	<10	103	5
5175E 2550N	1.4	1.72	572	86	<0.5	<5	0.05	15	23	<1	23	4.25	<1	0.12	12	0.22	3498	2	0.01	<1	2847	166	0.10	13	<1	5	<5	0.01	<10	<10	106	<10	73	4
5175E 2575N	<0.2	1.48	1813	188	1.3	<5	0.05	46	40	<1	90	9.14	<1	0.14	21	0.32	7021	<2	<0.01	<1	3274	351	0.08	28	5	6	<5	0.01	<10	19	153	<10	210	8
5175E 2600N	1.4	1.90	1330	150	0.6	<5	0.23	38	56	<1	149	8.67	<1	0.17	21	0.86	5140	<2	<0.01	<1	2673	370	0.11	28	5	10	<5	0.01	<10	12	187	<10	393	7
5175E 2650N	44.7	1.76	1333	78	<0.5	<5	0.09	36	49	<1	176	11.75	<1	0.15	21	0.51	6727	2	<0.01	<1	4486	2368	0.20	42	5	11	<5	0.02	<10	13	200	10	565	10
5175E 2675N	167.9	2.24	4299	91	0.7	<5	0.06	118	31	<1	51	9.44	<1	0.11	15	0.16	5490	<2	<0.01	<1	4675	1305	0.11	68	4	6	<5	0.01	<10	16	144	<10	419	12
5175E 2700N	<0.2	1.00	213	97	<0.5	<5	0.08	6	29	<1	143	6.98	<1	0.11	11	0.20	3445	<2	<0.01	<1	1250	430	0.14	14	4	4	<5	<0.01	<10	<10	136	<10	613	5
5175E 2725N	<0.2	0.85	31	38	<0.5	<5	0.09	<1	6	16	16	3.74	<1	0.04	<10	0.10	163	<2	<0.01	<1	1234	29	0.03	8	1	11	<5	0.11	<10	<10	166	<10	26	3
5175E 2750N	<0.2	1.30	48	57	<0.5	<5	0.06	1	9	15	9	6.58	<1	0.07	11	0.23	1431	3	<0.01	<1	2510	58	0.07	12	1	8	<5	0.10	<10	<10	149	<10	45	6
5175E 2775N	<0.2	1.59	45	83	<0.5	<5	0.17	1	16	27	24	6.42	<1	0.05	15	0.61	903	2	<0.01	17	1678	55	0.03	12	4	8	<5	0.01	<10	20	140	<10	142	7
5175E 2800N	1.1	0.62	57	83	<0.5	<5	0.07	1	4	10	12	2.14	<1	0.06	10	0.11	143	3	<0.01	1	777	32	0.04	6	1	5	<5	0.03	<10	<10	66	<10	45	2
5200E 2300N	<0.2	2.80	264	77	<0.5	<5	0.40	7	13	26	17	5.27	<1	0.06	20	0.51	1303	3	0.01	12	1467	61	0.09	12	2	19	<5	0.09	<10	59	117	<10	134	11
5200E 2325N	<0.2	1.68	71	43	<0.5	<5	0.08	2	5	21	7	3.15	<1	0.04	<10	0.23	172	17	<0.01	1	848	43	0.08	8	1	9	<5	0.11	<10	<10	106	<10	32	6
5200E 2350N	<0.2	2.66	616	56	<0.5	<5	0.09	16	14	29	23	7.08	<1	0.06	13	0.25	2169	3	0.02	<1	1779	79	0.11	16	1	8	<5	0.12	<10	19	186	<10	86	7
5200E 2375N	<0.2	2.12	131	65	<0.5	<5	0.06	4	8	15	25	4.62	<1	0.07	10	0.19	499	3	0.01	1	1229	52	0.07	10	1	7	<5	0.03	<10	<10	135	<10	80	3
5200E 2400N	<0.2	0.83	123	95	<0.5	<5	0.07	3	35	<1	16	5.93	<1	0.12	<10	0.12	7042	2	<0.01	<1	2688	124	0.08	11	1	9	<5	0.10	<10	<10	176	<10	58	4
5200E 2425N	<0.2	2.13	85	63	<0.5	<5	0.18	2	6	25	13	3.04	<1	0.09	14	0.51	420	2	0.02	10	2199	75	0.15	7	<1	10	<5	0.02	<10	<10	77	<10	76	3
5200E 2450N	<0.2	2.84	29	48	<0.5	<5	0.07	<1	9	42	15	6.08	<1	0.04	11	0.41	575	4	<0.01	6	1069	48	0.08	13	2	10	<5	0.14	<10	17	149	<10	61	11
5200E 2475N	<0.2	3.38	294	72	<0.5	<5	0.15	8	30	11	26	8.71	<1	0.08	12	0.33	1915	6	0.01	<1	2417	110	0.15	20	1	8	<5	0.05	<10	40	193	<10	74	6
5200E 2525N	<0.2	1.19	57	99	<0.5	<5	0.43	1	17	33	25	4.65	<1	0.05	12	0.77	792	<2	<0.01	27	1442	42	0.09	9	4	15	<5	0.01	<10	14	94	<10	125	4
5200E 2550N	3.0	1.50	2043	84	<0.5	<5	0.01	51	37	<1	48	8.06	<1	0.12	17	0.18	7332	<2	0.01	<1	2471	282	0.05	40	3	4	<5	0.01	<10	10	144	<10	127	8
5200E 2575N	<0.2	1.26	3816	124	1.0	<5	0.20	108	58	<1	236	13.06	<1	0.14	21	0.26	>10000	5	<0.01	<1	2861	4615	0.10	51	11	7	<5	<0.01	<10	41	195	10	598	10
5200E 2600N	4.1	2.23	2565	175	0.9	<5	0.07	69	33	<1	144	9.41	<1	0.12	20	0.55	5530	<2	<0.01	<1	2259	486	0.06	34	6	5	<5	<0.01	<10	13	178	<10	470	8
5200E 2625N	<0.2	1.37	809	219	0.5	<5	0.36	23	46	<1	53	7.31	<1	0.13	11	0.51	5771	3	<0.01	<1	3508	302	0.25	18	2	15	<5	0.01	<10	<10	134	<10	195	7
5200E 2650N	10.7	1.84	1818	84	0.5	<5	0.05	44	59	<1	89	9.94	<1	0.16	17	0.77	4071	4	<0.01	<1	4125	262	0.07	31	6	5	<5	0.01	<10	16	193	<10	220	9
5200E 2675N	<0.2	1.60	239	98	<0.5	<5	0.03	6	10	4	23	6.92	<1	0.08	16	0.11	1247	<2	0.01	<1	1126	114	0.04	13	2	5	<5	0.02	<10	13	155	<10	131	5
5200E 2700N	0.9	1.19	309	57	<0.5	<5	0.07	6	17	<1	146	6.10	<1	0.11	16	0.12	3706	<2	<0.01	<1	2327	3057	0.05	18	2	4	<5	0.01	<10	13	126	<10	545	5
5200E 2725N	<0.2	0.69	769	53	<0.5	<5	0.02	15	31	<1	36	7.46	<1	0.14	18	0.11	4023	2	<0.01	<1	3818	125	0.05	21	1	4	<5	0.01	<10	12	142	<10	74	5
5200E 2750N	<0.2	2.46	88	82	<0.5	6	0.09	2	16	6	19	6.86	<1	0.07	10	0.32	3132	4	<0.01	<1	2820	122	0.12	16	1	9	<5	0.10	<10	<10	221	<10	85	6

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3613SJ

Date : Oct-21-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment32

Sample type: Soil

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
5200E 2775N	20.4	1.54	574	75	<0.5	<5	0.05	12	14	<1	22	6.54	<1	0.05	10	0.26	2552	3	<0.01	<1	2171	167	0.05	19	1	6	<5	0.01	<10	<10	156	<10	104	4
5200E 2800N	<0.2	1.17	122	112	<0.5	<5	0.25	2	18	55	27	5.39	<1	0.06	12	0.83	1095	<2	<0.01	21	1494	67	0.06	13	2	9	<5	0.02	<10	<10	137	<10	130	4
5225E 2300N	<0.2	2.42	29	55	<0.5	<5	0.12	<1	15	79	17	6.90	<1	0.04	<10	0.85	711	<2	0.02	15	789	41	0.06	15	3	14	<5	0.18	<10	<10	217	<10	88	12
5225E 2325N	<0.2	1.99	684	70	<0.5	<5	0.03	14	22	<1	16	6.71	<1	0.09	<10	0.13	3271	<2	<0.01	<1	3273	80	0.12	14	<1	5	<5	0.01	<10	<10	201	<10	39	5
5225E 2350N	<0.2	2.59	25	43	<0.5	<5	0.06	<1	7	48	12	9.05	<1	0.05	19	0.21	425	4	0.03	<1	942	48	0.10	18	1	7	<5	0.17	<10	59	196	<10	55	64
5225E 2375N	<0.2	0.82	14	22	<0.5	<5	0.03	<1	2	11	3	0.74	<1	0.05	<10	0.04	87	2	<0.01	1	687	48	0.05	<5	<1	4	<5	0.06	<10	<10	37	<10	12	1
5225E 2400N	<0.2	2.28	5411	85	<0.5	<5	0.05	114	82	<1	66	11.95	<1	0.15	12	0.49	9123	4	<0.01	<1	6741	306	0.09	49	2	6	<5	0.05	<10	<10	317	<10	151	10
5225E 2425N	<0.2	1.57	47	46	<0.5	<5	0.09	<1	12	66	12	5.16	<1	0.03	<10	0.60	565	<2	0.02	13	1099	34	0.06	11	2	12	<5	0.13	<10	<10	183	<10	61	5
5225E 2450N	<0.2	2.26	33	61	<0.5	<5	0.35	<1	15	69	20	4.83	<1	0.04	10	0.76	745	<2	0.01	20	1119	37	0.04	11	3	17	<5	0.11	<10	<10	155	<10	98	5
5225E 2475N	<0.2	1.72	464	63	<0.5	<5	0.10	9	7	27	18	4.77	<1	0.04	13	0.14	819	3	<0.01	<1	1333	57	0.07	11	1	12	<5	0.06	<10	10	144	<10	49	5
5225E 2500N	<0.2	2.60	676	93	<0.5	<5	0.03	14	21	<1	22	10.15	<1	0.08	10	0.22	3993	5	0.02	<1	1329	215	0.09	23	1	4	<5	0.02	<10	13	218	<10	78	18
5225E 2525N	2.8	2.42	4113	103	1.7	<5	0.20	87	46	<1	86	10.80	<1	0.10	26	0.40	6023	2	<0.01	<1	3886	332	0.12	48	5	9	<5	0.01	<10	47	226	<10	233	14
5225E 2550N	0.8	2.48	1044	111	<0.5	<5	0.07	22	17	12	33	7.93	<1	0.07	10	0.25	1480	<2	<0.01	<1	2221	329	0.10	21	1	6	<5	0.01	<10	<10	250	<10	176	6
5225E 2575N	<0.2	2.37	2117	162	<0.5	<5	0.05	44	17	<1	29	9.80	<1	0.09	15	0.22	2561	<2	<0.01	<1	2082	202	0.04	28	2	4	<5	0.01	<10	<10	270	<10	114	7
5225E 2600N	<0.2	2.58	1819	84	<0.5	<5	0.04	39	34	<1	41	9.59	<1	0.09	14	0.49	5604	4	<0.01	<1	2603	515	0.07	27	6	6	<5	0.02	<10	20	251	<10	326	11
5225E 2625N	<0.2	1.99	1359	104	0.5	<5	0.34	30	48	<1	88	8.18	<1	0.13	15	0.82	5512	4	<0.01	<1	2517	344	0.09	25	4	10	<5	0.01	<10	<10	212	<10	218	8
5225E 2650N	17.4	2.00	2990	94	0.8	<5	0.01	59	73	<1	124	9.56	<1	0.12	21	0.53	7318	4	<0.01	<1	2744	365	0.06	38	8	4	<5	0.01	<10	15	229	<10	261	9
5225E 2675N	<0.2	2.36	560	84	<0.5	<5	0.08	11	29	<1	43	10.75	<1	0.09	14	0.36	3492	2	<0.01	<1	5269	522	0.08	26	3	8	<5	0.05	<10	<10	248	<10	265	8
5225E 2700N	<0.2	1.10	230	58	<0.5	<5	0.06	4	13	<1	13	6.76	<1	0.09	14	0.16	1827	2	<0.01	<1	2213	98	0.06	13	1	6	<5	0.07	<10	<10	184	<10	87	5
5225E 2725N	<0.2	1.08	257	79	<0.5	<5	0.01	7	9	<1	17	4.92	<1	0.13	19	0.07	1486	<2	<0.01	<1	3444	102	0.05	11	1	4	<5	<0.01	<10	28	74	<10	48	6
5225E 2750N	<0.2	0.95	208	56	<0.5	<5	0.11	5	19	<1	21	5.55	<1	0.09	12	0.10	2730	2	<0.01	<1	2165	127	0.06	12	1	12	<5	0.08	<10	<10	153	<10	57	4
5225E 2775N	<0.2	1.48	765	45	<0.5	<5	0.10	20	15	14	15	7.67	<1	0.08	<10	0.38	2639	<2	<0.01	3	3267	86	0.07	21	2	16	<5	0.16	<10	<10	203	<10	59	6
5225E 2800N	<0.2	0.86	452	226	<0.5	<5	0.49	12	13	11	24	5.57	<1	0.12	<10	0.31	1250	5	<0.01	<1	2095	68	0.10	15	1	24	<5	<0.01	<10	<10	103	<10	125	4
5250E 2300N	<0.2	1.57	91	92	<0.5	<5	0.04	2	24	<1	31	7.82	<1	0.11	<10	0.17	2263	2	<0.01	<1	1850	49	0.09	15	3	5	<5	<0.01	<10	<10	137	<10	147	7
5250E 2325N	<0.2	2.38	1025	62	<0.5	<5	0.07	27	36	7	44	9.30	<1	0.12	15	0.47	6278	4	0.03	<1	4420	137	0.12	25	3	8	<5	0.19	<10	20	250	<10	172	12
5250E 2350N	<0.2	2.23	23	49	<0.5	<5	0.12	<1	10	33	10	4.97	<1	0.04	10	0.47	557	2	<0.01	12	805	36	0.05	11	3	17	<5	0.15	<10	<10	159	<10	55	6
5250E 2375N	<0.2	2.33	15	51	<0.5	<5	0.13	<1	7	31	4	3.85	<1	0.05	<10	0.36	436	<2	<0.01	6	570	41	0.04	9	2	19	<5	0.14	<10	<10	127	<10	37	3
5250E 2400N	<0.2	2.56	77	58	<0.5	<5	0.21	1	11	42	16	6.93	<1	0.04	10	0.58	514	<2	<0.01	11	1117	43	0.07	15	3	19	<5	0.15	<10	10	173	<10	54	14
5250E 2425N	<0.2	2.37	26	60	<0.5	<5	0.13	<1	13	37	11	6.82	<1	0.03	12	0.63	501	<2	<0.01	12	557	46	0.05	16	3	19	<5	0.20	<10	14	177	<10	71	9
5250E 2450N	<0.2	2.80	25	39	<0.5	<5	0.11	<1	7	28	9	5.87	<1	0.08	18	0.23	357	6	0.04	<1	1407	58	0.08	13	1	6	<5	0.17	<10	91	116	<10	51	56

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3613SJ

Date : Oct-21-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment32

Sample type: Soil

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
5250E 2475N	<0.2	1.89	34	52	<0.5	<5	0.13	<1	12	30	8	5.77	<1	0.03	<10	0.47	475	<2	<0.01	8	539	38	0.03	13	3	22	<5	0.20	<10	<10	196	<10	47	5
5250E 2500N	<0.2	1.85	38	106	<0.5	<5	0.88	1	12	47	10	5.96	<1	0.05	<10	0.66	528	3	0.02	17	1090	34	0.08	13	3	46	<5	0.13	<10	<10	151	<10	103	6
5250E 2525N	<0.2	2.35	2910	131	1.1	<5	0.12	79	40	<1	81	9.15	<1	0.15	31	0.31	6375	4	<0.01	<1	3118	268	0.08	33	2	10	<5	0.02	<10	55	172	<10	275	16
5250E 2550N	<0.2	2.74	525	82	<0.5	<5	0.03	13	39	3	80	10.57	<1	0.13	20	0.29	2890	3	<0.01	<1	1945	110	0.07	24	2	5	<5	0.01	<10	39	190	<10	147	14
5250E 2575N	2.2	1.18	158	69	<0.5	<5	0.07	4	14	9	14	3.47	<1	0.10	10	0.13	1263	<2	<0.01	<1	1627	68	0.05	10	1	10	<5	0.05	<10	<10	101	<10	38	2
5250E 2600N	<0.2	2.33	1650	121	<0.5	<5	0.01	42	9	15	16	8.73	<1	0.11	10	0.16	683	7	<0.01	<1	973	97	0.04	22	3	5	<5	0.02	<10	<10	317	<10	50	6
5250E 2625N	<0.2	1.77	1207	116	0.6	<5	0.10	34	32	<1	110	13.17	<1	0.19	31	0.39	5840	6	<0.01	<1	3236	152	0.05	39	13	6	<5	0.01	<10	76	202	<10	205	16
5250E 2650N	15.8	1.66	3131	205	1.0	<5	0.11	89	74	<1	177	11.45	<1	0.20	24	0.50	7287	4	<0.01	<1	4057	347	0.09	49	7	7	<5	0.01	<10	29	203	<10	502	11
5250E 2675N	<0.2	2.01	1013	87	<0.5	<5	0.02	26	43	15	58	11.92	<1	0.15	18	0.94	2425	<2	<0.01	<1	3829	175	0.09	40	6	7	<5	0.01	<10	28	236	<10	141	10
5250E 2700N	<0.2	1.25	143	58	<0.5	<5	0.10	3	11	16	10	5.59	<1	0.09	10	0.30	1196	2	<0.01	2	1720	56	0.06	12	2	14	<5	0.11	<10	<10	152	<10	51	5
5250E 2725N	<0.2	0.92	2033	153	0.7	<5	0.02	53	56	<1	142	>15.00	<1	0.14	26	0.17	4121	<2	<0.01	<1	4761	208	0.08	55	3	11	<5	0.01	<10	51	222	<10	151	12
5250E 2750N	5.3	0.45	664	58	<0.5	<5	0.01	18	29	<1	55	5.13	<1	0.11	13	0.07	3504	<2	0.02	<1	2080	195	0.03	17	2	3	<5	0.01	<10	23	80	<10	92	4
5250E 2775N	<0.2	1.19	117	74	<0.5	<5	0.03	3	21	<1	47	6.02	<1	0.08	<10	0.12	4851	<2	0.02	<1	2372	52	0.07	11	1	5	<5	0.04	<10	<10	180	<10	83	4
5250E 2800N	4.6	0.83	206	164	<0.5	<5	0.27	6	18	22	52	5.48	<1	0.06	<10	0.67	1269	<2	0.02	15	1243	92	0.33	14	3	11	<5	0.02	<10	12	108	<10	160	4
5275E 2300N	<0.2	1.29	1955	281	<0.5	<5	0.03	49	26	<1	47	7.60	<1	0.09	<10	0.12	>10000	<2	0.03	<1	2572	83	0.11	25	1	5	<5	0.01	<10	<10	231	<10	64	5
5275E 2325N	<0.2	1.63	692	65	<0.5	<5	0.05	18	22	<1	27	5.75	<1	0.09	<10	0.25	3832	<2	0.04	<1	3430	53	0.11	12	<1	4	<5	0.02	<10	<10	166	<10	37	4
5275E 2350N	<0.2	1.93	450	54	<0.5	<5	0.04	12	43	<1	96	6.72	<1	0.10	10	0.44	>10000	3	0.04	<1	2807	232	0.05	18	3	5	<5	0.03	<10	<10	192	<10	90	5
5275E 2375N	<0.2	1.56	23	40	<0.5	<5	0.19	<1	13	27	19	4.42	<1	0.03	<10	0.70	632	<2	0.03	22	558	30	0.02	10	3	15	<5	0.13	<10	<10	122	<10	74	5
5275E 2400N	<0.2	1.40	23	55	<0.5	<5	0.24	<1	14	29	24	3.61	<1	0.03	<10	0.72	732	<2	0.02	24	1075	28	0.01	8	4	15	<5	0.11	<10	10	107	<10	88	4
5275E 2425N	<0.2	1.66	18	34	<0.5	<5	0.09	<1	11	39	9	6.15	<1	0.02	<10	0.58	539	<2	0.02	15	737	34	0.04	12	2	14	<5	0.12	<10	<10	171	<10	59	5
5275E 2450N	<0.2	1.24	10	73	<0.5	<5	0.24	<1	8	23	5	2.92	<1	0.03	<10	0.45	370	2	0.02	10	520	22	0.04	6	1	15	<5	0.08	<10	<10	85	<10	77	2
5275E 2475N	<0.2	1.58	40	34	<0.5	<5	0.07	1	8	30	7	4.48	<1	0.03	<10	0.29	693	<2	0.03	5	990	36	0.04	10	1	9	<5	0.11	<10	<10	139	<10	35	4
5275E 2500N	<0.2	1.33	41	34	<0.5	<5	0.07	1	10	25	12	5.49	<1	0.03	<10	0.32	992	<2	0.03	7	711	96	0.05	11	1	11	<5	0.11	<10	<10	137	<10	67	6
5275E 2525N	<0.2	1.56	212	59	<0.5	<5	0.08	5	25	<1	31	4.50	<1	0.10	10	0.19	5130	2	0.03	<1	1953	104	0.04	10	1	3	<5	0.03	<10	<10	128	<10	62	3
5275E 2550N	11.8	1.52	1426	221	0.6	<5	0.20	45	58	<1	205	7.29	<1	0.15	21	0.46	>10000	5	0.02	1	2337	391	0.05	22	11	9	<5	0.01	<10	27	160	<10	350	7
5275E 2575N	18.4	0.64	670	143	<0.5	<5	0.03	18	9	<1	29	3.36	<1	0.11	<10	0.05	2916	<2	0.01	<1	1846	236	0.13	17	<1	8	<5	0.01	<10	<10	85	<10	44	2
5275E 2600N	1.9	1.09	2047	48	<0.5	<5	0.03	51	36	<1	75	7.93	<1	0.08	11	0.42	3364	<2	0.02	<1	2051	181	0.04	29	4	6	<5	0.02	<10	17	152	<10	85	7
5275E 2625N	<0.2	1.18	1110	62	<0.5	<5	0.05	29	12	7	23	4.22	<1	0.10	<10	0.23	1110	2	0.02	<1	1743	69	0.07	20	<1	4	<5	0.01	<10	<10	98	<10	42	3
5275E 2650N	2.4	0.62	1845	92	<0.5	<5	0.02	47	25	<1	23	7.07	<1	0.08	<10	0.08	>10000	<2	0.05	<1	4121	122	0.09	30	2	4	<5	0.01	<10	<10	118	<10	99	5
5275E 2675N	<0.2	1.59	463	69	<0.5	<5	0.01	12	41	3	70	10.95	<1	0.08	12	0.83	3138	3	0.01	<1	2768	196	0.11	27	6	5	<5	0.01	<10	16	219	<10	130	8

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3613SJ

Date : Oct-21-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment32

Sample type: Soil

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
5275E 2700N	<0.2	1.35	117	41	<0.5	<5	0.11	3	7	35	12	4.36	<1	0.05	<10	0.48	399	<2	0.03	11	1450	50	0.03	9	1	11	<5	0.08	<10	<10	130	<10	48	4
5275E 2725N	28.9	0.62	807	66	<0.5	<5	0.01	22	27	<1	34	5.84	<1	0.09	10	0.07	4334	<2	0.02	<1	2393	339	0.03	28	2	3	<5	0.01	<10	10	102	<10	52	6
5275E 2750N	1.2	0.74	949	73	<0.5	<5	0.01	23	30	<1	71	7.20	<1	0.10	13	0.14	3284	<2	0.02	<1	2415	139	0.06	22	3	3	<5	0.01	<10	22	124	<10	123	6
5275E 2775N	<0.2	1.11	264	88	<0.5	5	0.02	6	18	<1	64	9.77	<1	0.09	<10	0.19	3073	2	0.02	<1	4811	77	0.09	17	1	5	<5	0.01	<10	<10	168	<10	116	8
5275E 2800N	25.3	0.66	476	152	<0.5	<5	0.25	13	18	17	70	5.41	<1	0.06	<10	0.51	1524	2	0.01	11	1179	270	0.34	23	3	11	<5	0.01	<10	11	100	<10	220	4
5300E 2300N	<0.2	1.42	909	87	<0.5	<5	0.05	22	12	9	28	4.34	<1	0.09	<10	0.24	1039	2	<0.01	1	1790	43	0.08	11	1	5	<5	0.03	<10	<10	189	<10	44	3
5300E 2325N	1.7	1.00	142	63	<0.5	<5	0.03	4	6	8	22	2.36	<1	0.08	<10	0.09	599	<2	0.01	<1	979	37	0.06	6	<1	4	<5	0.01	<10	<10	99	<10	21	2
5300E 2350N	<0.2	1.69	44	21	<0.5	<5	0.10	1	5	20	17	3.81	<1	0.06	17	0.15	399	10	0.09	2	1356	42	0.12	9	<1	5	<5	0.10	<10	70	71	<10	65	39
5300E 2375N	<0.2	1.19	19	26	<0.5	<5	0.06	<1	5	23	5	2.09	<1	0.05	10	0.25	159	4	<0.01	5	989	39	0.07	5	1	5	<5	0.10	<10	36	62	<10	37	14
5300E 2400N	<0.2	1.44	35	63	<0.5	<5	0.23	<1	15	38	29	4.03	<1	0.05	<10	0.82	987	<2	0.03	27	1303	40	0.01	9	4	13	<5	0.08	<10	13	114	<10	104	4
5300E 2425N	<0.2	1.48	19	31	<0.5	<5	0.07	<1	5	33	6	3.86	<1	0.02	<10	0.27	236	<2	0.04	4	566	28	0.03	8	2	9	<5	0.11	<10	16	120	<10	34	6
5300E 2450N	<0.2	2.14	31	48	<0.5	<5	0.10	<1	8	40	13	6.02	<1	0.02	<10	0.42	466	<2	0.03	12	828	50	0.06	13	2	12	<5	0.11	<10	<10	149	<10	52	7
5300E 2475N	<0.2	1.44	33	32	<0.5	<5	0.05	<1	9	32	7	6.24	<1	0.03	<10	0.33	750	<2	0.03	7	1580	38	0.05	13	2	9	<5	0.16	<10	12	164	<10	45	9
5300E 2500N	<0.2	1.61	32	37	<0.5	<5	0.07	<1	10	36	13	5.55	<1	0.03	<10	0.56	733	<2	0.02	13	1324	36	0.04	11	2	11	<5	0.11	<10	<10	151	<10	62	5
5300E 2525N	<0.2	1.04	817	161	<0.5	<5	0.03	21	61	<1	105	10.96	<1	0.14	10	0.45	5209	<2	0.03	<1	3845	210	0.16	31	4	9	<5	0.01	<10	17	204	<10	115	11
5300E 2550N	29.7	1.33	1030	135	<0.5	<5	0.20	30	39	2	206	10.80	<1	0.19	13	0.50	2902	3	0.03	<1	3256	648	0.36	44	7	16	<5	0.03	<10	19	227	10	706	10
5300E 2575N	44.2	1.66	73	25	<0.5	<5	0.04	2	3	7	31	1.18	<1	0.05	<10	0.05	66	<2	0.02	2	2768	28	0.15	5	<1	3	<5	0.01	<10	<10	24	<10	18	2
5300E 2600N	<0.2	1.81	239	34	<0.5	<5	0.05	6	7	34	23	6.08	<1	0.06	26	0.53	499	2	0.05	6	1564	70	0.09	12	2	5	<5	0.07	<10	46	132	<10	65	9
5300E 2625N	<0.2	0.71	745	61	<0.5	<5	0.02	20	4	9	21	5.84	<1	0.07	<10	0.10	272	<2	<0.01	<1	1719	42	0.07	16	1	5	<5	0.02	<10	<10	146	<10	30	4
5300E 2650N	<0.2	2.18	264	52	<0.5	<5	0.04	6	40	<1	26	8.84	<1	0.06	<10	0.28	>10000	3	<0.01	<1	2317	83	0.10	18	1	6	<5	0.06	<10	<10	235	<10	45	6
5300E 2675N	<0.2	1.95	907	51	<0.5	<5	0.05	24	28	11	40	8.68	<1	0.06	12	0.64	2750	5	0.04	<1	2425	90	0.09	25	2	8	<5	0.03	<10	12	197	<10	90	6
5300E 2700N	<0.2	1.62	19	54	<0.5	<5	0.24	<1	12	31	15	3.78	<1	0.03	<10	0.70	577	<2	0.03	20	786	29	0.02	8	3	15	<5	0.10	<10	<10	105	<10	77	3
5300E 2725N	34.2	1.08	6282	72	<0.5	5	0.05	177	33	3	101	11.92	<1	0.08	14	0.37	3504	<2	0.03	<1	2477	433	0.14	79	4	7	<5	0.02	<10	22	221	<10	208	10
5300E 2750N	4.0	1.03	2085	77	<0.5	<5	0.05	56	9	11	23	4.39	<1	0.09	10	0.20	1109	<2	0.02	<1	2121	123	0.03	25	1	4	<5	0.02	<10	17	87	<10	53	3
5300E 2775N	<0.2	1.34	159	97	0.7	<5	0.03	4	29	<1	62	5.73	<1	0.08	14	0.16	2804	4	0.02	<1	2145	78	0.04	13	4	4	<5	0.01	<10	39	102	<10	106	7
5300E 2800N	5.0	1.05	993	338	0.8	<5	0.50	27	35	<1	98	7.43	<1	0.12	18	0.52	3310	2	<0.01	6	2120	186	0.23	23	4	22	<5	0.02	<10	20	129	<10	443	7

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

*Quality Assaying for over 35 Years***Assay Certificate****8V-3633-RA1**Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deanne**

Oct-23-08

We hereby certify the following assay of 22 rock samples
submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121868	1.74	1.68	5.5
121869	1.97		7.1
121870	0.98		3.1
121871	0.80		<0.1
121872	0.61		<0.1
121873	1.23		0.7
121874	1.49		7.1
121875	0.01		4.1
121876	0.07		<0.1
121877	0.05	0.06	<0.1
121878	0.14		<0.1
121879	0.23		2.0
121880	0.27		1.9
121881	0.15		0.5
121882	0.03		<0.1
121883	0.05		0.3
121884	0.04		2.9
121885	0.03		<0.1
121886	0.04		<0.1
121887	0.03	0.04	<0.1
121888	0.01		<0.1
121889	0.02		<0.1
*0211	2.12		
*BLANK	<0.01		

Certified by _____

*Quality Assaying for over 35 Years***Assay Certificate****8V-3633-RA2**Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deanne**

Oct-23-08

We hereby certify the following assay of 22 rock samples
submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121890	0.06	0.05	<0.1
121891	0.59		0.5
121892	0.15		<0.1
121893	0.02		<0.1
121894	0.01		<0.1
121895	0.01		<0.1
121896	0.01		<0.1
121897	0.03		<0.1
121898	0.08		<0.1
121899	0.46	0.48	<0.1
121900	0.50		<0.1
121901	1.49		<0.1
121902	1.16		<0.1
121903	0.08		<0.1
121904	0.33		<0.1
121905	0.46		<0.1
121906	0.76		<0.1
121907	0.68		<0.1
121908	0.22		<0.1
121909	0.18	0.16	<0.1
121909A	0.01		<0.1
121910	0.03		<0.1
*0211	2.23		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 35 Years

Assay Certificate

8V-3633-RA3


Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deanne**

Oct-23-08

We hereby certify the following assay of 22 rock samples submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
121911	0.02	0.02	<0.1	
121912	0.01		<0.1	
121913	0.02		<0.1	
121914	0.01		<0.1	
121915	0.06		<0.1	
121916	0.09		<0.1	
121917	0.03		<0.1	
121918	0.11		<0.1	1.30
121919	0.01		<0.1	
121920	0.02	0.02	<0.1	
121921	0.06		<0.1	
121922	0.02		<0.1	
121923	0.01		<0.1	
121924	0.01		<0.1	
121925	<0.01		3.0	
121926	0.01		<0.1	
121927	0.01		<0.1	
121928	0.03		<0.1	
121929	0.01		<0.1	
121930	0.03	0.03	<0.1	
121931	0.01		<0.1	
121932	0.02		<0.1	
*0211	2.15			
*CCu-1c				3.95
*BLANK	<0.01			<0.01

Certified by _____





Quality Assaying for over 35 Years

Assay Certificate

8V-3633-RA4

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deanne**

Oct-23-08

We hereby certify the following assay of 22 rock samples submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
121933	0.02	0.02	0.3	
121934	0.01		0.4	
121935	0.02		1.2	
121936	0.01		0.2	
121937	0.01		0.4	
121938	<0.01		<0.1	
121939	<0.01		<0.1	
121940	0.02		0.3	
121941	0.02		0.3	
121942	0.02	<0.01	<0.1	
121943	0.03		<0.1	
121944	0.04		0.2	
121945	0.01		<0.1	
121946	0.01		0.3	
121947	0.01		0.4	
121948	0.01		0.1	
121949	0.01		0.5	
121950	0.18		>200	801.0
121951	0.02		2.1	
121952	0.05	0.04	2.3	
121953	0.02		0.6	
121954	0.02		0.4	
*0211	2.17			
*CCu-1c				129.8
*BLANK	<0.01			<0.1

Certified by _____

Quality Assaying for over 35 Years

Assay Certificate

8V-3633-RA5


Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deanne**

Oct-23-08

We hereby certify the following assay of 22 rock samples submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %	Zn %
121955	0.02	0.02	0.1		
121956	0.01		<0.1		
121957	0.02		<0.1		
121958	0.01		<0.1		
121959	0.02		0.1		
121960	0.44		7.9		
121961	0.48		76.3	3.29	3.03
121962	0.02		0.1		
121963	0.02		0.3		
121964	0.01	<0.01	<0.1		
121965	0.01		0.1		
121966	0.01		0.2		
121967	0.01		0.3		
122138	0.03		0.5		
122139	0.05		0.4		
122140	0.01		0.1		
122141	0.03		0.3		
122142	0.01		<0.1		
122143	0.01		0.3		
122144	0.03	0.02	0.5		
122145	0.01		0.2		
122146	0.03		<0.1		
*0211	2.16				
*CCu-1c				0.34	3.96
*BLANK	<0.01			<0.01	<0.01

Certified by _____



*Quality Assaying for over 35 Years***Assay Certificate****8V-3633-RA6**Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deanne****Oct-23-08**We hereby certify the following assay of 22 rock samples
submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122147	0.02	0.02	0.3
122148	0.04		0.5
122149	0.01		0.3
122150	0.01		<0.1
122151	<0.01		0.2
122152	0.02		0.3
122153	0.01		0.2
122154	0.02		0.1
122155	0.03		0.2
122156	0.01	0.01	0.2
122157	0.04		0.4
122158	<0.01		0.1
122159	0.07		0.5
122160	0.04		0.5
122161	0.02		0.3
122162	0.01		0.3
122163	0.01		0.3
122164	0.02		0.3
122165	0.04		0.5
122166	0.02	0.03	0.6
122167	0.01		0.2
122168	0.01		0.1
*0211	2.14		
*BLANK	<0.01		

Certified by _____



Quality Assaying for over 35 Years

Assay Certificate

8V-3633-RA7

Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deanne**

Oct-23-08

We hereby certify the following assay of 22 rock samples submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
122169	0.01	0.01	0.1	
122170	0.01		0.6	
122171	0.01		0.5	
122172	0.03		0.5	
122173	<0.01		0.6	
122174	0.04		1.1	
122175	0.16		>200	800.0
122176	0.03		1.4	
122177	0.03		0.7	
122178	0.03	0.03	0.8	
122179	0.04		1.0	
122180	0.01		0.6	
122601	0.10		2.8	
122602	0.08		2.1	
122603	0.08		1.3	
122604	0.04		0.3	
122605	0.01		0.2	
122606	0.01		0.2	
122607	<0.01		0.3	
122608	0.04	0.04	0.4	
122609	0.02		0.7	
122610	0.62		2.1	
*0211	2.25			
*CCu-1c				127.9
*BLANK	<0.01			<0.1

Certified by _____

*Quality Assaying for over 35 Years***Assay Certificate****8V-3633-RA8**Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deanne**

Oct-23-08

We hereby certify the following assay of 22 rock samples
submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122611	0.04	0.04	0.3
122612	0.04		0.5
122613	0.04		0.3
122614	0.02		0.5
122615	0.06		0.5
122616	0.05		0.9
122617	0.03		0.9
122618	0.02		0.4
122619	0.03		1.1
122620	0.03	0.04	0.8
122621	0.03		0.9
122622	0.10		2.4
122623	0.06		1.4
122624	0.06		1.6
122625	0.04		1.3
122626	0.01		0.3
122627	0.01		0.1
122628	0.04		0.2
122629	0.04		0.3
122630	0.01	0.01	0.2
122631	0.02		0.2
122632	0.01		0.3
*0211	2.07		
*BLANK	<0.01		

Certified by _____

*Quality Assaying for over 35 Years***Assay Certificate****8V-3633-RA9**Company: **Ascot Resources Ltd.**
Project: **Dilworth**
Attn: **Sue Deanne**

Oct-23-08

We hereby certify the following assay of 22 rock samples
submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122633	0.02	0.04	0.4
122634	0.02		0.6
122635	0.04		0.6
122636	0.01		0.4
122637	0.01		0.5
122638	0.01		0.6
122639	0.02		0.6
122640	0.01		0.9
122641	0.03		0.6
122642	0.11	0.11	1.0
122643	0.02		1.6
122644	0.01		1.1
122645	0.01		0.8
122646	0.04		0.8
122647	<0.01		0.8
122648	0.02		0.8
122649	0.02		1.0
122650	0.03		0.9
122651	0.17		1.0
122652	0.42	0.39	0.9
*0211	2.23		
*BLANK	<0.01		

Certified by _____



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3633RJ

Date : Oct-23-08

Sample type : Rock

Ascot Resources Ltd.

Project : Dilworth

Attention : Sue Deanne

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121868	5.5	2.00	82	71	<0.5	<5	8.13	6	17	9	706	5.87	<1	0.23	<10	1.16	2872	64	0.02	<1	0.103	58	1.21	11	5	132	<5	0.02	<10	<10	211	<10	626	4
121869	7.1	1.56	127	65	<0.5	<5	8.17	11	14	30	952	5.30	<1	0.17	<10	0.93	2615	74	0.03	<1	0.096	104	1.13	10	6	132	<5	0.01	<10	<10	189	11	803	4
121870	3.1	1.79	40	81	<0.5	<5	4.11	17	15	12	766	5.06	<1	0.26	<10	1.01	1894	59	0.03	<1	0.131	422	0.75	11	5	75	<5	0.05	<10	<10	203	21	1491	4
121871	<0.2	2.00	138	58	<0.5	<5	8.53	11	17	<1	695	5.95	<1	0.18	<10	1.20	2798	28	0.04	<1	0.105	57	1.32	11	6	135	<5	0.05	<10	<10	224	12	777	4
121872	<0.2	1.99	130	90	<0.5	<5	6.84	9	15	114	463	5.38	<1	0.22	<10	1.40	2774	28	0.04	<1	0.108	64	1.20	11	7	120	<5	0.03	<10	<10	204	14	1000	4
121873	0.7	2.07	178	54	<0.5	<5	5.18	19	15	7	933	6.77	<1	0.12	<10	1.24	2763	7	0.03	<1	0.112	117	1.58	13	7	97	<5	0.05	<10	<10	276	16	1167	5
121874	7.1	2.07	212	65	<0.5	<5	5.21	29	21	11	1236	7.38	<1	0.15	<10	1.25	2659	26	0.04	<1	0.115	104	2.28	14	6	102	<5	0.02	<10	<10	271	26	1991	5
121875	4.1	0.06	11	12	<0.5	13	16.00	<1	1	11	11	0.13	<1	0.01	<10	2.21	110	2	<0.01	1	0.008	<2	0.09	<5	<1	5936	<5	<0.01	<10	<10	6	<10	16	<1
121876	<0.2	2.28	52	121	<0.5	<5	7.11	3	15	<1	162	6.02	<1	0.30	<10	1.61	2906	13	0.02	<1	0.110	128	0.78	11	4	116	<5	<0.01	<10	<10	193	<10	481	4
121877	<0.2	2.30	26	107	<0.5	<5	4.48	23	16	<1	246	5.93	<1	0.30	<10	1.66	2406	12	0.02	<1	0.116	694	0.98	12	4	91	<5	0.02	<10	<10	201	39	2992	4
121878	<0.2	2.02	81	104	<0.5	<5	6.63	6	17	67	265	5.30	<1	0.29	<10	1.45	2565	24	0.03	1	0.117	158	1.14	11	6	110	<5	0.02	<10	<10	200	10	709	4
121879	2.0	1.58	125	100	<0.5	<5	5.68	12	21	196	299	4.79	<1	0.20	<10	1.21	2034	49	<0.01	10	0.139	282	1.69	12	9	87	<5	0.01	<10	<10	225	18	1277	3
121880	1.9	1.22	216	57	<0.5	<5	8.83	14	17	398	295	4.20	<1	0.13	<10	1.02	2868	37	0.02	13	0.097	88	1.85	12	9	136	<5	0.01	<10	<10	198	19	1406	4
121881	0.5	1.72	241	75	<0.5	<5	9.98	10	29	688	401	5.63	<1	0.15	<10	1.38	3323	38	<0.01	35	0.161	63	1.61	16	18	188	<5	0.02	<10	<10	303	<10	535	4
121882	<0.2	1.96	144	61	<0.5	<5	14.90	8	32	880	187	5.20	<1	0.08	<10	1.67	3772	75	<0.01	34	0.153	35	0.65	15	23	241	<5	0.05	<10	<10	359	11	536	6
121883	0.3	1.80	152	49	<0.5	<5	13.58	9	34	856	318	4.66	<1	0.07	<10	1.63	3057	57	<0.01	42	0.153	39	0.84	16	20	183	<5	0.08	<10	<10	343	<10	551	5
121884	2.9	1.30	95	41	<0.5	<5	23.35	8	22	546	283	3.68	<1	0.05	<10	1.11	4224	12	0.01	22	0.110	21	0.65	12	18	227	<5	0.06	<10	<10	269	<10	514	4
121885	<0.2	2.08	108	28	<0.5	<5	17.09	4	28	784	192	5.05	<1	0.07	<10	1.88	3572	105	0.01	33	0.134	33	0.52	13	21	197	<5	0.03	<10	<10	317	<10	256	4
121886	<0.2	2.19	75	35	<0.5	<5	10.37	8	32	814	262	5.48	<1	0.06	<10	2.07	2706	30	<0.01	34	0.156	34	0.67	17	16	192	<5	0.10	<10	<10	326	<10	523	6
121887	<0.2	2.23	59	43	<0.5	<5	7.00	7	29	1091	161	5.26	<1	0.06	<10	2.44	2092	5	<0.01	38	0.181	39	0.35	18	14	127	<5	0.12	<10	<10	370	<10	486	6
121888	<0.2	2.23	43	52	<0.5	<5	8.98	3	27	996	85	4.92	<1	0.08	<10	2.50	1771	2	0.01	37	0.186	31	0.14	15	14	177	<5	0.12	<10	<10	337	<10	259	5
121889	<0.2	2.09	55	43	<0.5	<5	9.00	12	30	975	39	4.75	<1	0.06	<10	2.38	1963	2	<0.01	46	0.176	29	0.27	15	15	156	<5	0.12	<10	<10	353	10	597	5
121890	<0.2	2.53	103	26	<0.5	<5	10.87	19	35	898	296	6.06	<1	0.06	<10	2.48	2769	15	0.01	39	0.150	59	0.91	17	23	182	<5	0.06	<10	<10	400	16	1073	5
121891	0.5	1.94	110	39	<0.5	<5	8.89	10	21	423	478	5.73	<1	0.12	<10	1.53	2510	24	0.03	16	0.121	63	1.42	14	15	111	<5	0.07	<10	<10	280	11	780	5
121892	<0.2	2.16	127	33	<0.5	<5	12.11	27	27	681	232	5.83	<1	0.06	<10	2.08	3094	8	<0.01	26	0.136	705	1.46	16	18	208	<5	0.07	<10	<10	341	32	2372	6
121893	<0.2	2.74	54	38	<0.5	<5	10.44	11	25	631	78	6.51	<1	0.11	<10	2.44	2511	2	0.01	25	0.170	48	0.51	15	20	178	<5	0.08	<10	<10	397	12	773	6
121894	<0.2	2.28	34	38	<0.5	<5	9.54	9	19	213	39	5.22	<1	0.24	<10	1.79	1821	<2	0.02	10	0.147	98	0.47	12	11	151	<5	0.11	<10	<10	234	11	676	4
121895	<0.2	2.91	20	42	<0.5	<5	7.53	2	22	202	113	6.55	<1	0.21	<10	2.41	1962	<2	0.03	10	0.179	49	0.27	14	12	119	<5	0.12	<10	<10	294	<10	305	5
121896	<0.2	2.33	26	43	<0.5	<5	9.82	3	25	137	70	5.17	<1	0.22	<10	1.91	1817	3	0.04	13	0.150	48	0.40	12	10	140	<5	0.07	<10	<10	216	<10	273	4
121897	<0.2	2.67	24	50	<0.5	<5	6.69	1	27	212	80	5.92	<1	0.22	<10	2.49	1789	2	0.02	13	0.164	42	0.39	13	10	120	<5	0.06	<10	<10	289	<10	171	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3633RJ

Date : Oct-23-08

Sample type : Rock

Ascot Resources Ltd.

Project : Dilworth

Multi-Element ICP-AES Analysis

Attention : Sue Deanne

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121898	<0.2	2.31	58	57	<0.5	<5	6.57	4	22	152	73	5.91	<1	0.27	<10	1.84	1973	3	0.01	13	0.144	227	1.33	12	8	97	<5	0.06	<10	<10	233	<10	465	4
121899	<0.2	1.85	52	49	<0.5	<5	7.36	3	20	101	225	5.45	<1	0.27	<10	1.25	1706	27	0.03	9	0.103	52	0.92	12	7	96	<5	0.02	<10	<10	189	<10	397	4
121900	<0.2	1.00	6529	23	<0.5	18	8.34	138	176	43	67	4.21	<1	0.06	<10	0.29	726	16	<0.01	36	0.136	19	1.40	12	2	89	<5	0.06	<10	11	111	<10	107	12
121901	<0.2	2.53	30	95	<0.5	<5	3.33	3	23	28	424	7.25	<1	0.29	<10	1.48	1534	110	0.03	<1	0.121	68	0.80	14	6	62	<5	0.08	<10	<10	240	<10	466	5
121902	<0.2	2.00	26	50	<0.5	<5	4.82	10	19	46	371	5.75	<1	0.26	<10	1.20	1854	48	0.04	<1	0.115	81	0.91	11	5	69	<5	0.08	<10	<10	196	14	864	4
121903	<0.2	1.78	34	55	<0.5	<5	10.11	4	14	<1	104	4.69	<1	0.32	<10	1.00	2350	6	0.02	<1	0.100	68	0.85	9	3	299	<5	0.07	<10	<10	151	<10	419	3
121904	<0.2	1.87	25	62	<0.5	<5	4.74	2	19	22	152	4.90	<1	0.35	<10	1.16	1832	6	0.05	<1	0.124	63	0.80	10	4	94	<5	0.07	<10	<10	166	<10	289	3
121905	<0.2	2.24	18	85	<0.5	<5	5.53	11	19	<1	305	6.10	<1	0.34	<10	1.37	2305	14	0.03	<1	0.130	100	0.77	11	5	101	<5	0.05	<10	<10	207	13	896	4
121906	<0.2	1.99	126	74	<0.5	<5	5.58	11	19	<1	298	6.10	<1	0.30	<10	1.36	2588	40	0.04	<1	0.126	125	0.74	11	4	146	<5	0.01	<10	<10	204	11	758	4
121907	<0.2	1.87	19	66	<0.5	<5	6.28	10	18	<1	314	5.32	<1	0.26	<10	1.15	2155	23	0.08	<1	0.120	73	0.57	9	5	110	<5	0.03	<10	<10	191	12	891	4
121908	<0.2	1.97	53	88	<0.5	<5	4.79	4	21	<1	149	5.39	<1	0.35	<10	1.26	2122	5	0.04	<1	0.137	56	1.00	11	4	102	<5	0.06	<10	<10	196	<10	354	4
121909	<0.2	2.49	529	86	<0.5	<5	5.37	21	21	<1	87	7.15	<1	0.32	<10	1.67	2907	3	0.03	<1	0.126	317	1.98	14	4	181	<5	0.03	<10	<10	228	20	1474	5
121909A	<0.2	2.25	21	73	<0.5	<5	7.13	<1	19	<1	49	5.27	<1	0.37	<10	1.46	2275	<2	0.07	<1	0.138	41	0.39	10	4	155	<5	0.07	<10	<10	173	<10	139	4
121910	<0.2	2.08	63	86	<0.5	<5	5.61	5	20	<1	77	5.22	<1	0.41	<10	1.38	2051	<2	0.05	<1	0.145	67	0.68	11	4	129	<5	0.09	<10	<10	172	11	494	4
121911	<0.2	2.28	22	88	<0.5	<5	5.95	<1	19	<1	58	5.49	<1	0.38	<10	1.49	1886	<2	0.07	<1	0.136	45	0.42	10	4	129	<5	0.08	<10	<10	191	<10	110	4
121912	<0.2	2.27	21	85	<0.5	<5	5.26	1	20	<1	49	5.65	<1	0.31	<10	1.54	2037	<2	0.07	<1	0.139	49	0.33	10	4	131	<5	0.05	<10	<10	205	<10	221	4
121913	<0.2	2.33	11	84	<0.5	<5	5.62	<1	21	<1	67	5.97	<1	0.33	<10	1.47	1876	<2	0.07	<1	0.128	35	0.54	10	5	122	<5	0.05	<10	<10	213	<10	120	4
121914	<0.2	2.22	16	81	<0.5	<5	5.70	<1	17	<1	48	5.44	<1	0.35	<10	1.41	1910	<2	0.08	<1	0.133	34	0.45	9	4	123	<5	0.04	<10	<10	184	<10	100	4
121915	<0.2	2.16	132	104	<0.5	<5	4.86	5	17	<1	44	5.99	<1	0.32	<10	1.35	2481	<2	0.05	<1	0.127	140	1.20	11	4	90	<5	0.01	<10	<10	206	<10	451	4
121916	<0.2	1.95	36	86	<0.5	<5	4.30	7	17	<1	34	4.68	<1	0.35	<10	1.50	2139	<2	0.01	<1	0.104	122	0.67	8	3	91	<5	0.01	<10	<10	140	14	1113	4
121917	<0.2	2.55	58	94	<0.5	<5	5.07	27	24	<1	36	7.05	<1	0.27	<10	1.96	2902	<2	0.03	<1	0.123	852	1.49	13	4	125	<5	0.01	<10	<10	245	47	3744	5
121918	<0.2	1.67	141	102	<0.5	<5	2.46	111	24	5	104	6.67	<1	0.35	<10	1.32	2035	5	0.01	<1	0.115	2799	3.43	12	3	65	<5	<0.01	<10	<10	176	197	>10000	4
121919	<0.2	2.24	16	96	<0.5	<5	6.64	1	19	<1	67	6.23	<1	0.36	<10	1.56	2082	<2	0.05	<1	0.137	76	0.42	9	5	167	<5	0.01	<10	<10	206	<10	236	4
121920	<0.2	2.19	19	131	<0.5	<5	5.09	3	21	<1	60	5.99	<1	0.35	<10	1.68	2146	<2	0.04	<1	0.132	123	0.69	10	5	145	<5	0.01	<10	<10	186	<10	551	4
121921	<0.2	2.01	15	101	<0.5	<5	6.21	5	16	<1	41	4.81	<1	0.41	<10	1.28	1954	<2	0.04	<1	0.127	580	0.57	9	4	125	<5	0.03	<10	<10	156	10	691	3
121922	<0.2	2.06	15	92	<0.5	<5	5.00	<1	16	<1	43	4.86	<1	0.34	<10	1.36	1676	<2	0.06	<1	0.126	39	0.32	9	5	133	<5	0.05	<10	<10	173	<10	104	4
121923	<0.2	2.42	11	91	<0.5	<5	6.54	<1	18	<1	46	5.29	<1	0.32	<10	1.87	1898	<2	0.07	<1	0.120	74	0.45	10	5	156	<5	0.07	<10	<10	194	<10	126	4
121924	<0.2	1.97	12	84	<0.5	<5	3.92	<1	17	<1	25	4.96	<1	0.33	<10	1.29	1639	<2	0.04	<1	0.132	113	0.48	10	4	99	<5	0.07	<10	<10	162	<10	179	4
121925	3.0	0.15	8	12	<0.5	9	16.50	<1	1	60	2	0.32	<1	0.05	<10	6.79	184	<2	<0.01	6	0.020	<2	0.05	<5	<1	2288	<5	<0.01	<10	<10	11	<10	9	<1
121926	<0.2	2.18	22	64	<0.5	<5	6.26	<1	26	<1	19	4.34	<1	0.31	<10	1.78	1546	<2	0.06	1	0.132	52	0.24	9	4	143	<5	0.11	<10	<10	158	<10	98	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3633RJ

Date : Oct-23-08

Sample type : Rock

Ascot Resources Ltd.

Project : Dilworth

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Attention : Sue Deanne

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121927	<0.2	2.10	19	64	<0.5	<5	6.48	<1	21	<1	21	4.58	<1	0.30	<10	1.56	1659	<2	0.09	<1	0.123	41	0.26	9	4	166	<5	0.08	<10	<10	154	<10	91	3
121928	<0.2	3.63	25	117	<0.5	<5	4.37	4	28	<1	118	9.16	<1	0.21	<10	2.84	2795	<2	0.05	<1	0.115	1058	1.58	21	7	160	<5	0.01	<10	<10	349	11	690	7
121929	<0.2	1.94	11	53	<0.5	<5	16.77	<1	14	<1	5	4.27	<1	0.26	<10	1.40	2047	<2	0.07	<1	0.095	33	0.28	8	4	788	<5	<0.01	<10	<10	150	<10	80	3
121930	<0.2	1.91	8	74	<0.5	<5	2.29	<1	19	1	45	5.17	<1	0.29	<10	1.27	1459	<2	0.03	<1	0.129	61	0.74	10	5	113	<5	0.03	<10	<10	186	<10	107	4
121931	<0.2	2.01	8	61	<0.5	<5	3.31	<1	16	<1	33	5.16	<1	0.22	<10	1.37	1504	<2	0.06	<1	0.122	38	0.55	10	5	119	<5	0.09	<10	<10	211	<10	95	4
121932	<0.2	2.12	13	70	<0.5	<5	2.93	<1	17	<1	36	5.55	<1	0.30	<10	1.41	1642	<2	0.08	<1	0.130	56	0.73	11	5	105	<5	0.08	<10	<10	203	<10	102	4
121933	0.3	2.52	22	61	<0.5	<5	2.99	1	19	11	51	5.98	<1	0.21	<10	1.62	1917	<2	0.02	1	0.133	75	0.77	13	4	95	<5	0.11	<10	<10	95	<10	119	4
121934	0.4	2.28	16	64	<0.5	<5	5.21	1	15	4	38	4.60	<1	0.27	<10	1.54	1893	<2	0.02	1	0.122	71	0.54	10	3	140	<5	0.08	<10	<10	63	<10	102	2
121935	1.2	2.31	34	66	<0.5	<5	5.25	<1	16	25	35	4.96	<1	0.22	<10	1.53	2248	4	0.01	5	0.121	627	0.74	11	4	145	<5	0.04	<10	<10	70	<10	98	2
121936	0.2	2.16	12	66	<0.5	<5	3.61	<1	16	5	35	4.86	<1	0.24	<10	1.39	1872	<2	0.02	2	0.132	50	0.55	10	3	113	<5	0.06	<10	<10	69	<10	88	2
121937	0.4	2.23	9	68	<0.5	<5	3.32	<1	16	4	48	5.04	<1	0.21	<10	1.39	1875	<2	0.03	2	0.128	133	0.42	10	4	109	<5	0.05	<10	<10	82	<10	198	3
121938	<0.2	2.33	15	69	<0.5	<5	5.02	<1	17	5	22	4.55	<1	0.22	<10	1.46	1682	<2	0.03	1	0.129	25	0.29	10	4	176	<5	0.09	<10	<10	73	<10	81	4
121939	<0.2	2.76	20	152	<0.5	<5	2.67	<1	19	8	38	4.83	<1	0.57	<10	1.21	1384	<2	0.14	2	0.138	32	0.54	11	5	107	<5	0.14	<10	<10	96	<10	89	4
121940	0.3	2.15	23	128	<0.5	<5	3.97	1	14	11	43	4.16	<1	0.47	<10	1.15	1268	<2	0.06	2	0.119	88	0.82	8	5	106	<5	0.05	<10	<10	86	<10	162	3
121941	0.3	2.82	32	197	<0.5	<5	2.91	1	18	33	42	4.88	<1	0.81	<10	1.14	1466	<2	0.10	3	0.124	115	0.93	11	5	103	<5	0.12	<10	<10	85	<10	168	3
121942	<0.2	2.34	13	76	<0.5	<5	4.11	<1	20	5	18	5.38	<1	0.30	<10	1.41	1953	<2	0.03	2	0.131	43	0.51	11	5	127	<5	0.13	<10	<10	81	<10	93	3
121943	<0.2	2.27	15	68	<0.5	<5	4.65	<1	20	5	32	5.48	<1	0.24	<10	1.31	1893	<2	0.02	2	0.137	27	0.43	11	5	156	<5	0.12	<10	<10	79	<10	91	3
121944	0.2	2.11	16	80	<0.5	<5	4.66	<1	17	4	27	4.94	<1	0.27	<10	1.18	1936	<2	0.02	2	0.130	63	0.45	10	4	127	<5	0.12	<10	<10	68	<10	136	3
121945	<0.2	1.86	9	84	<0.5	<5	4.91	<1	18	6	30	4.52	<1	0.25	<10	0.99	1627	<2	0.03	2	0.130	26	0.46	9	4	159	<5	0.13	<10	<10	67	<10	76	3
121946	0.3	2.03	14	81	<0.5	<5	3.29	1	17	15	29	4.98	<1	0.21	<10	1.21	1964	<2	0.02	3	0.130	77	0.53	10	4	92	<5	0.11	<10	<10	76	<10	333	3
121947	0.4	1.82	19	126	<0.5	<5	3.46	2	17	4	23	5.15	<1	0.28	<10	0.88	1896	<2	0.02	2	0.135	175	1.24	10	4	105	<5	0.12	<10	<10	68	<10	352	3
121948	<0.2	1.82	14	141	<0.5	<5	4.05	1	15	5	18	4.45	<1	0.34	<10	0.78	1804	<2	0.02	1	0.134	67	0.64	9	3	127	<5	0.12	<10	<10	60	<10	166	3
121949	0.5	2.06	29	104	<0.5	<5	5.17	4	17	4	30	4.94	<1	0.26	<10	1.14	2352	<2	0.02	1	0.124	211	0.66	10	3	122	<5	0.08	<10	<10	64	10	565	2
121950	>200.0	0.57	545	172	<0.5	65	0.52	19	7	18	7594	2.11	5	0.15	<10	0.55	268	548	0.03	4	0.024	889	1.07	1640	2	73	<5	0.05	<10	<10	18	<10	957	2
121951	2.1	1.81	26	115	<0.5	<5	5.65	1	17	4	29	4.52	<1	0.32	<10	0.90	2488	<2	0.02	1	0.135	59	0.78	13	3	106	<5	0.10	<10	<10	57	<10	161	2
121952	2.3	1.71	79	74	<0.5	<5	11.48	2	13	9	16	4.93	<1	0.23	<10	1.01	4172	<2	0.01	1	0.088	122	1.49	12	3	203	<5	0.07	<10	<10	47	<10	248	2
121953	0.6	2.03	21	89	<0.5	<5	4.51	<1	16	5	31	4.73	<1	0.34	<10	1.12	1808	<2	0.02	1	0.133	58	0.61	10	3	122	<5	0.10	<10	<10	51	<10	107	3
121954	0.4	2.01	40	93	<0.5	<5	4.46	1	17	6	10	5.04	<1	0.33	<10	1.03	2097	<2	0.02	1	0.136	63	0.75	10	3	133	<5	0.10	<10	<10	51	<10	144	2
121955	<0.2	1.92	13	131	<0.5	<5	4.60	1	19	25	31	5.05	<1	0.42	<10	0.86	1927	<2	0.02	3	0.162	60	0.70	<5	3	136	<5	0.11	<10	<10	59	<10	115	3
121956	<0.2	2.04	6	105	<0.5	<5	3.89	1	18	14	24	5.33	<1	0.30	<10	1.13	1797	<2	0.02	3	0.156	70	0.58	<5	4	109	<5	0.09	<10	<10	62	<10	122	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3633RJ

Date : Oct-23-08

Sample type : Rock

Ascot Resources Ltd.

Project : Dilworth

Attention : Sue Deanne

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121957	<0.2	2.08	5	107	<0.5	<5	5.21	<1	18	19	13	4.99	<1	0.31	<10	1.18	1932	<2	0.02	4	0.156	25	0.39	<5	4	155	<5	0.12	<10	<10	60	<10	92	3
121958	<0.2	1.85	8	146	<0.5	<5	5.49	<1	17	14	26	4.48	<1	0.38	<10	0.96	1834	<2	0.02	3	0.146	37	0.49	<5	4	169	<5	0.12	<10	<10	49	<10	85	3
121959	<0.2	2.13	8	120	<0.5	<5	4.69	<1	20	6	26	5.48	<1	0.34	<10	1.16	1975	<2	0.02	3	0.158	73	0.75	<5	3	128	<5	0.11	<10	10	55	<10	105	3
121960	7.9	1.79	113	107	<0.5	<5	9.24	75	16	24	445	5.55	<1	0.27	<10	1.00	3204	<2	0.01	3	0.117	3182	2.52	<5	2	469	<5	0.06	<10	22	36	138	8368	2
121961	76.3	1.92	229	82	<0.5	<5	12.03	285	18	11	927	6.99	2	0.21	<10	1.22	4611	<2	0.01	2	0.105	>10000	5.58	31	2	294	<5	0.07	<10	30	47	516	>10000	2
121962	<0.2	2.12	12	126	<0.5	<5	5.16	1	18	20	27	5.10	<1	0.38	<10	1.17	2034	<2	0.02	4	0.145	78	0.57	<5	3	154	<5	0.10	<10	10	49	<10	164	3
121963	0.3	2.00	9	116	<0.5	<5	5.21	1	17	7	19	4.99	<1	0.34	<10	1.12	1884	<2	0.02	2	0.159	172	0.62	<5	3	161	<5	0.12	<10	<10	51	<10	177	2
121964	<0.2	2.15	5	126	<0.5	<5	4.43	1	20	8	19	5.33	<1	0.36	<10	1.17	1825	<2	0.02	3	0.160	47	0.62	<5	3	198	<5	0.13	<10	<10	57	<10	116	3
121965	<0.2	1.97	21	129	<0.5	<5	5.22	<1	18	20	16	4.66	<1	0.37	<10	1.05	1991	<2	0.02	4	0.161	50	0.52	<5	3	294	<5	0.10	<10	<10	45	<10	98	2
121966	0.2	2.13	25	150	<0.5	<5	5.33	<1	18	7	16	5.27	<1	0.34	<10	1.16	2457	<2	0.02	3	0.157	31	0.52	<5	3	166	<5	0.04	<10	11	56	<10	97	2
121967	0.3	2.31	26	175	<0.5	<5	4.66	<1	23	16	20	5.76	<1	0.38	<10	1.28	2350	<2	0.02	4	0.156	87	0.81	<5	3	167	<5	0.07	<10	11	58	<10	108	3
122138	0.5	0.34	37	165	<0.5	<5	3.93	1	8	81	3	2.99	<1	0.23	<10	0.80	1561	<2	0.01	3	0.097	19	0.42	<5	2	227	<5	<0.01	<10	<10	9	<10	70	1
122139	0.4	0.61	104	214	<0.5	<5	3.06	2	16	23	24	4.28	<1	0.33	<10	0.77	1311	<2	0.02	3	0.137	25	1.59	<5	4	179	<5	<0.01	<10	<10	13	<10	63	2
122140	<0.2	1.13	17	209	<0.5	<5	2.66	<1	16	21	26	4.63	<1	0.33	<10	0.97	1386	<2	0.02	3	0.138	22	1.14	<5	4	117	<5	<0.01	<10	<10	25	<10	75	2
122141	0.3	0.48	17	171	<0.5	<5	9.44	<1	14	22	28	3.86	<1	0.29	<10	0.72	2304	<2	0.02	2	0.114	15	1.32	<5	4	750	<5	<0.01	<10	11	12	<10	59	2
122142	<0.2	1.39	22	203	<0.5	<5	2.94	<1	14	15	19	4.58	<1	0.33	<10	0.95	1597	<2	0.03	3	0.133	11	0.93	<5	4	122	<5	<0.01	<10	<10	28	<10	85	2
122143	0.3	1.46	38	181	<0.5	<5	2.58	1	13	16	21	4.38	<1	0.28	<10	1.00	1556	<2	0.03	3	0.133	11	0.96	<5	4	112	<5	<0.01	<10	<10	35	<10	91	2
122144	0.5	0.72	50	177	<0.5	<5	4.20	1	12	30	17	4.11	<1	0.30	<10	0.87	1722	<2	0.02	3	0.125	13	0.71	<5	4	220	<5	<0.01	<10	<10	17	<10	89	2
122145	0.2	1.45	32	197	<0.5	<5	3.87	1	13	12	17	4.15	<1	0.29	<10	0.92	1806	<2	0.02	2	0.137	9	0.48	<5	4	147	<5	<0.01	<10	<10	33	<10	97	2
122146	<0.2	1.52	17	203	<0.5	<5	2.07	<1	12	23	16	4.34	<1	0.26	11	0.88	1625	<2	0.03	3	0.140	7	0.20	<5	4	82	<5	<0.01	<10	<10	36	<10	133	2
122147	0.3	1.66	14	208	<0.5	<5	2.29	<1	12	13	21	3.96	<1	0.28	<10	0.92	1386	<2	0.02	2	0.128	17	0.31	7	3	94	<5	<0.01	<10	<10	35	<10	103	2
122148	0.5	1.00	36	140	<0.5	<5	2.35	<1	11	49	6	3.74	<1	0.32	<10	0.47	1102	<2	0.02	2	0.116	20	2.24	7	2	124	<5	<0.01	<10	<10	21	<10	55	2
122149	0.3	1.58	21	207	<0.5	<5	2.62	<1	11	12	24	3.75	<1	0.34	<10	0.84	1263	<2	0.02	1	0.125	15	0.52	7	3	138	<5	<0.01	<10	<10	30	<10	80	2
122150	<0.2	0.05	6	12	<0.5	10	16.00	<1	1	4	1	0.06	<1	0.02	<10	2.25	46	<2	0.01	<1	0.006	<2	0.10	<5	<1	5876	<5	<0.01	<10	22	1	<10	2	<1
122151	0.2	1.59	10	225	<0.5	<5	3.06	<1	13	9	23	3.88	<1	0.36	12	0.87	1236	<2	0.03	1	0.137	15	0.19	7	3	154	<5	<0.01	<10	<10	29	<10	91	2
122152	0.3	1.41	26	193	<0.5	<5	3.65	<1	12	13	22	3.77	<1	0.34	<10	0.83	1220	<2	0.02	2	0.127	17	0.77	7	3	152	<5	<0.01	<10	<10	27	<10	97	2
122153	0.2	1.33	29	221	<0.5	<5	3.88	<1	11	13	20	3.53	<1	0.37	<10	0.81	1315	<2	0.02	1	0.124	16	0.44	6	3	198	<5	<0.01	<10	<10	22	<10	85	2
122154	<0.2	1.46	14	299	<0.5	<5	3.71	<1	12	14	24	3.64	<1	0.30	10	0.81	1296	<2	0.04	1	0.123	13	0.19	7	4	265	<5	0.05	<10	<10	37	<10	82	3
122155	0.2	1.52	47	232	<0.5	<5	3.54	1	13	15	21	3.81	<1	0.29	10	0.89	1397	<2	0.03	1	0.131	19	0.40	7	4	269	<5	0.05	<10	<10	37	<10	76	3
122156	0.2	1.54	21	230	<0.5	<5	3.83	<1	11	10	22	3.63	<1	0.35	11	0.72	1265	<2	0.03	1	0.128	14	0.24	6	3	243	<5	0.01	<10	<10	29	<10	76	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3633RJ

Date : Oct-23-08

Sample type : Rock

Ascot Resources Ltd.

Project : Dilworth

Attention : Sue Deanne

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122157	0.4	1.33	82	234	<0.5	<5	3.51	1	12	14	19	3.46	<1	0.36	<10	0.75	1383	<2	0.02	1	0.120	24	0.55	6	2	159	<5	<0.01	<10	<10	23	<10	75	2
122158	<0.2	1.67	20	176	<0.5	<5	3.30	<1	12	11	18	3.91	<1	0.26	10	1.08	1340	<2	0.03	1	0.125	15	0.30	7	3	127	<5	<0.01	<10	<10	39	<10	88	2
122159	0.5	1.44	100	177	<0.5	<5	2.15	2	12	24	20	4.22	<1	0.31	<10	0.83	1096	<2	0.02	2	0.126	23	0.95	9	2	80	<5	<0.01	<10	<10	28	<10	90	2
122160	0.5	1.15	79	225	0.5	<5	3.49	2	13	18	21	3.63	<1	0.33	<10	0.72	1269	<2	0.02	2	0.131	21	1.31	8	2	143	<5	<0.01	<10	<10	23	<10	94	2
122161	0.3	1.31	47	171	<0.5	<5	3.02	1	12	22	21	3.66	<1	0.32	<10	0.75	1151	<2	0.02	2	0.123	16	1.24	7	2	110	<5	<0.01	<10	<10	26	<10	75	2
122162	0.3	1.45	29	180	<0.5	<5	3.72	<1	12	14	16	3.67	<1	0.35	<10	0.75	1344	<2	0.02	2	0.124	17	0.93	7	2	138	<5	0.01	<10	<10	25	<10	88	2
122163	0.3	1.53	46	187	<0.5	<5	3.22	<1	13	9	20	3.75	<1	0.34	10	0.74	1339	<2	0.02	1	0.124	16	0.45	8	3	154	<5	0.05	<10	<10	31	<10	91	3
122164	0.3	1.57	49	190	<0.5	<5	3.03	1	13	10	27	3.80	<1	0.32	10	0.76	1325	<2	0.03	1	0.125	17	0.37	8	3	155	<5	0.05	<10	<10	36	<10	95	3
122165	0.5	1.50	76	206	<0.5	<5	1.22	1	14	14	19	3.90	<1	0.37	<10	0.69	938	<2	0.02	2	0.130	21	0.86	9	2	62	<5	0.01	<10	<10	30	<10	82	2
122166	0.6	1.44	76	199	<0.5	<5	2.04	1	13	14	16	3.86	<1	0.37	<10	0.67	1095	<2	0.02	2	0.126	24	0.91	9	2	92	<5	0.01	<10	<10	29	<10	101	2
122167	0.2	1.43	28	208	<0.5	<5	3.17	<1	12	19	17	3.48	<1	0.37	<10	0.68	1282	<2	0.02	2	0.129	16	0.42	7	2	246	<5	<0.01	<10	<10	25	<10	84	2
122168	<0.2	1.66	17	208	<0.5	<5	3.47	<1	11	9	18	3.93	<1	0.35	10	0.82	1227	<2	0.03	1	0.127	17	0.29	7	3	224	<5	0.01	<10	<10	31	<10	93	2
122169	<0.2	1.61	15	176	<0.5	<5	2.91	<1	12	15	23	4.14	<1	0.33	10	0.88	1170	<2	0.03	2	0.133	17	0.47	7	3	144	<5	<0.01	<10	<10	33	<10	92	2
122170	0.6	1.14	20	147	<0.5	<5	5.14	<1	11	15	25	3.97	<1	0.31	<10	0.74	1555	3	0.03	1	0.119	15	0.83	7	3	284	<5	<0.01	<10	<10	23	<10	77	2
122171	0.5	1.19	40	170	<0.5	<5	4.27	<1	13	26	19	3.73	<1	0.35	<10	0.74	1365	<2	0.02	2	0.128	15	0.66	7	3	225	<5	<0.01	<10	<10	21	<10	64	2
122172	0.5	1.83	66	152	<0.5	<5	4.28	1	14	15	25	4.42	<1	0.32	<10	0.91	1540	<2	0.02	2	0.131	20	0.64	9	3	145	<5	0.03	<10	<10	34	<10	93	3
122173	0.6	1.95	23	171	<0.5	<5	3.92	<1	16	12	23	4.61	<1	0.33	11	0.98	1631	<2	0.02	2	0.139	20	0.55	10	3	128	<5	0.07	<10	<10	35	<10	104	3
122174	1.1	1.45	85	143	<0.5	<5	4.84	1	14	15	20	4.84	<1	0.29	<10	0.79	1496	<2	0.02	1	0.124	28	2.20	9	2	136	<5	0.04	<10	<10	24	<10	111	3
122175	>200.0	0.59	580	180	<0.5	78	0.57	20	7	19	7974	2.35	5	0.15	<10	0.60	277	564	0.03	4	0.026	946	1.16	1839	1	76	<5	0.05	<10	<10	19	<10	1055	2
122176	1.4	1.63	53	134	<0.5	<5	3.11	1	14	16	28	4.29	<1	0.26	<10	0.97	1426	<2	0.02	2	0.125	28	1.12	12	2	98	<5	0.09	<10	<10	29	<10	145	3
122177	0.7	1.63	53	137	<0.5	<5	3.30	1	14	14	22	4.36	<1	0.27	10	0.89	1439	<2	0.02	2	0.128	20	1.14	10	2	102	<5	0.08	<10	<10	30	<10	96	3
122178	0.8	1.88	92	119	<0.5	<5	3.39	1	14	14	21	4.64	<1	0.25	10	1.04	1612	<2	0.03	1	0.120	21	0.77	11	2	94	<5	0.09	<10	<10	35	<10	96	3
122179	1.0	1.68	245	148	<0.5	<5	4.09	5	15	13	21	4.13	<1	0.30	10	0.80	1537	<2	0.02	2	0.128	20	1.00	12	3	122	<5	0.08	<10	<10	32	<10	86	3
122180	0.6	1.77	73	146	<0.5	<5	3.02	1	15	17	19	4.63	<1	0.28	<10	0.95	1385	<2	0.02	2	0.124	21	1.10	11	2	92	<5	0.07	<10	<10	33	<10	91	3
122601	2.8	2.22	106	92	<0.5	<5	4.19	3	22	12	103	6.28	<1	0.28	<10	1.30	2017	22	0.02	2	0.145	54	1.28	11	4	168	<5	0.01	<10	<10	84	<10	277	3
122602	2.1	2.00	102	101	<0.5	<5	3.63	3	20	15	86	6.22	<1	0.28	<10	1.27	1949	9	0.02	2	0.151	44	1.76	11	5	138	<5	0.01	<10	<10	83	<10	273	3
122603	1.3	2.33	71	143	<0.5	<5	5.99	1	22	13	73	5.65	<1	0.26	10	1.38	2395	<2	0.02	2	0.165	312	0.51	11	5	152	<5	0.02	<10	<10	81	<10	122	2
122604	0.3	2.56	31	147	<0.5	<5	3.91	<1	26	12	49	6.55	<1	0.20	11	1.55	2277	<2	0.03	2	0.179	35	0.59	12	6	107	<5	0.04	<10	<10	111	<10	151	3
122605	0.2	2.71	20	141	<0.5	<5	4.19	1	25	10	52	6.65	<1	0.23	10	1.59	2317	<2	0.03	2	0.184	36	0.65	12	6	145	<5	0.04	<10	<10	119	24	178	3
122606	0.2	2.32	31	153	<0.5	<5	2.99	1	23	14	59	6.35	<1	0.22	<10	1.41	1995	<2	0.03	2	0.182	37	0.97	11	5	109	<5	0.02	<10	<10	103	<10	240	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3633RJ

Date : Oct-23-08

Sample type : Rock

Ascot Resources Ltd.

Project : Dilworth

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Attention : Sue Deanne

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122607	0.3	2.37	27	132	<0.5	<5	4.75	1	23	11	50	6.22	<1	0.17	<10	1.38	2250	<2	0.03	2	0.173	30	0.65	12	6	140	<5	0.01	<10	<10	110	<10	255	3
122608	0.4	0.59	47	171	0.5	<5	2.49	1	23	11	42	4.65	<1	0.37	<10	0.09	672	2	0.01	2	0.234	14	0.33	9	6	23	<5	<0.01	<10	<10	21	<10	50	2
122609	0.7	0.69	68	358	<0.5	<5	4.00	5	25	44	35	7.00	<1	0.33	11	0.16	2116	2	0.02	3	0.219	17	0.04	15	6	33	<5	<0.01	<10	<10	28	10	540	3
122610	2.1	1.61	141	186	<0.5	<5	0.34	3	13	28	22	5.16	<1	0.24	10	0.67	1272	<2	0.02	2	0.149	35	0.26	14	2	9	<5	<0.01	<10	<10	26	<10	387	2
122611	0.3	1.85	14	150	<0.5	<5	3.91	<1	11	19	34	4.17	<1	0.21	10	1.05	1471	<2	0.03	2	0.120	21	0.84	7	2	126	<5	<0.01	<10	<10	37	<10	96	2
122612	0.5	1.90	12	132	<0.5	<5	3.65	<1	12	24	51	4.44	<1	0.19	11	1.09	1454	<2	0.03	2	0.124	23	0.90	8	2	142	<5	<0.01	<10	<10	43	<10	95	2
122613	0.3	1.75	17	138	<0.5	<5	4.48	<1	11	20	37	3.93	<1	0.21	11	0.96	1449	<2	0.03	2	0.119	21	0.58	8	2	183	<5	<0.01	<10	<10	38	<10	79	2
122614	0.5	1.63	18	123	<0.5	<5	3.60	<1	11	19	48	4.04	<1	0.20	10	0.91	1415	<2	0.03	1	0.119	24	0.82	8	2	133	<5	0.01	<10	<10	43	<10	105	2
122615	0.5	1.67	18	147	<0.5	<5	3.74	<1	12	16	60	3.97	<1	0.23	10	0.92	1393	<2	0.02	1	0.123	18	0.62	7	3	128	<5	<0.01	<10	<10	38	<10	98	2
122616	0.9	1.41	25	142	0.5	<5	4.93	<1	12	19	113	3.93	<1	0.28	10	0.75	1411	2	0.02	1	0.125	20	0.70	7	2	174	<5	<0.01	<10	<10	30	<10	113	2
122617	0.9	1.27	18	191	0.5	<5	3.92	<1	12	14	123	3.79	<1	0.32	11	0.64	1267	2	0.02	2	0.166	21	0.64	7	2	140	<5	<0.01	<10	<10	29	<10	97	2
122618	0.4	1.75	33	88	<0.5	<5	5.30	<1	11	23	29	3.91	<1	0.18	<10	1.00	1397	<2	0.03	2	0.115	24	0.40	8	3	195	<5	0.01	<10	<10	51	<10	81	2
122619	1.1	1.50	87	80	0.5	<5	4.78	2	11	8	62	4.33	<1	0.15	<10	0.97	1500	<2	0.02	1	0.125	26	1.58	8	2	167	<5	<0.01	<10	<10	33	<10	175	2
122620	0.8	1.68	22	135	<0.5	<5	4.88	<1	12	14	56	3.98	<1	0.25	<10	0.91	1558	2	0.02	1	0.128	25	0.94	8	2	158	<5	0.01	<10	<10	32	<10	118	2
122621	0.9	1.64	47	127	0.5	<5	3.97	1	12	15	45	3.98	<1	0.24	<10	0.91	1383	<2	0.02	2	0.126	22	1.11	9	2	148	<5	<0.01	<10	<10	35	<10	108	2
122622	2.4	1.42	93	132	<0.5	<5	0.49	2	14	28	132	4.26	<1	0.29	<10	0.70	850	6	0.02	2	0.122	33	1.72	11	2	30	<5	<0.01	<10	<10	30	<10	159	2
122623	1.4	1.04	110	96	<0.5	<5	0.38	3	14	26	65	4.20	<1	0.29	<10	0.50	548	2	0.02	2	0.122	35	2.88	10	1	26	<5	<0.01	<10	<10	19	<10	140	2
122624	1.6	1.19	103	112	<0.5	<5	0.35	2	15	35	82	4.08	<1	0.28	<10	0.64	656	2	0.02	3	0.122	38	2.29	11	1	27	<5	<0.01	<10	<10	27	<10	135	2
122625	1.3	1.20	142	123	<0.5	<5	0.35	3	14	34	36	4.09	<1	0.29	<10	0.62	669	<2	0.02	3	0.125	33	2.24	12	1	24	<5	<0.01	<10	<10	24	<10	136	2
122626	0.3	1.85	20	78	<0.5	<5	4.05	1	16	16	40	4.11	<1	0.36	10	1.12	1678	<2	0.01	2	0.141	50	0.68	10	2	119	<5	0.11	<10	<10	45	<10	115	3
122627	<0.2	1.96	15	73	<0.5	<5	3.51	<1	17	15	33	4.38	<1	0.24	<10	1.15	1648	<2	0.02	2	0.142	23	0.19	10	4	132	<5	0.12	<10	<10	58	<10	70	3
122628	0.2	2.17	22	74	<0.5	<5	3.47	<1	18	10	44	4.59	<1	0.29	<10	1.36	1672	<2	0.02	2	0.140	40	0.24	10	3	100	<5	0.10	<10	<10	59	<10	87	2
122629	0.3	2.08	44	76	<0.5	<5	3.54	1	19	9	32	4.85	<1	0.26	10	1.31	1750	<2	0.02	2	0.147	45	0.44	10	3	103	<5	0.09	<10	<10	61	<10	92	2
122630	0.2	2.07	33	54	<0.5	<5	5.36	<1	17	11	37	4.64	<1	0.26	<10	1.37	1874	<2	0.02	2	0.140	27	0.31	9	3	124	<5	0.08	<10	<10	60	<10	93	2
122631	0.2	2.18	22	55	<0.5	<5	4.58	<1	18	19	49	4.86	<1	0.23	<10	1.50	2064	<2	0.02	2	0.148	35	0.21	10	4	155	<5	0.10	<10	<10	72	<10	100	2
122632	0.3	2.16	15	68	<0.5	<5	3.63	<1	19	8	58	5.09	<1	0.25	<10	1.42	1957	<2	0.02	2	0.158	37	0.48	10	3	136	<5	0.10	<10	<10	69	<10	102	3
122633	0.4	2.30	44	93	<0.5	<5	4.32	<1	19	15	7	4.57	<1	0.34	<10	1.66	2647	<2	0.01	2	0.154	50	0.44	11	3	108	<5	0.12	<10	<10	57	<10	84	2
122634	0.6	2.47	106	127	<0.5	<5	4.56	2	18	16	9	5.09	<1	0.35	11	1.69	2860	<2	0.01	2	0.160	87	0.58	11	3	122	<5	0.10	<10	<10	57	<10	90	2
122635	0.6	2.11	63	97	<0.5	<5	4.14	1	18	15	25	4.29	<1	0.36	<10	1.30	2414	<2	0.01	2	0.145	67	0.58	11	3	117	<5	0.11	<10	<10	51	<10	92	2
122636	0.4	2.45	41	111	<0.5	<5	4.68	<1	21	11	46	5.21	<1	0.28	<10	1.65	2428	<2	0.02	2	0.166	44	0.43	13	5	117	<5	0.15	<10	<10	88	<10	95	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3633RJ

Date : Oct-23-08

Sample type : Rock

Ascot Resources Ltd.

Project : Dilworth

Attention : Sue Deanne

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122637	0.5	2.46	57	68	<0.5	<5	4.12	1	22	10	41	5.57	<1	0.23	<10	1.66	2098	<2	0.02	2	0.175	41	0.55	13	4	102	<5	0.14	<10	<10	86	<10	96	3
122638	0.6	2.37	51	101	<0.5	<5	3.40	<1	22	16	48	5.32	<1	0.33	10	1.52	2130	<2	0.02	2	0.176	32	0.41	13	4	83	<5	0.15	<10	<10	72	<10	85	3
122639	0.6	2.25	107	101	<0.5	<5	4.15	2	21	12	53	5.16	<1	0.28	10	1.57	2294	<2	0.02	2	0.172	40	0.79	12	4	103	<5	0.15	<10	<10	80	13	85	3
122640	0.9	2.21	33	228	<0.5	<5	5.12	<1	16	8	43	4.63	<1	0.42	<10	1.01	2211	<2	0.03	2	0.147	21	0.48	10	2	118	<5	0.02	<10	<10	30	<10	94	2
122641	0.6	2.39	29	192	<0.5	<5	6.51	<1	15	5	11	5.16	<1	0.33	<10	1.23	2786	<2	0.03	1	0.146	22	0.53	10	3	147	<5	0.03	<10	<10	40	<10	110	2
122642	1.0	2.35	94	209	<0.5	<5	4.70	2	16	7	21	5.35	<1	0.35	<10	1.22	2811	<2	0.03	1	0.152	27	1.18	11	2	132	<5	0.03	<10	<10	42	<10	116	2
122643	1.6	2.19	65	210	<0.5	<5	5.33	1	16	8	78	4.66	<1	0.35	<10	1.14	2993	<2	0.03	2	0.175	28	1.07	10	3	134	<5	0.02	<10	<10	38	<10	108	2
122644	1.1	1.94	30	187	<0.5	<5	7.05	<1	12	8	59	3.57	<1	0.34	<10	1.09	2798	<2	0.04	1	0.170	31	0.60	8	2	200	<5	0.05	<10	<10	29	<10	89	1
122645	0.8	2.74	33	162	<0.5	5	7.90	<1	20	7	4	5.30	<1	0.27	<10	1.93	3900	<2	0.03	2	0.144	33	0.64	12	4	243	<5	0.08	<10	<10	50	<10	109	2
122646	0.8	3.22	67	113	<0.5	<5	8.32	<1	35	49	105	6.00	<1	0.22	<10	2.94	2515	<2	0.03	31	0.097	31	0.88	15	15	310	<5	0.20	<10	<10	153	<10	81	4
122647	0.8	3.51	59	178	<0.5	<5	6.82	<1	39	52	107	6.26	<1	0.24	<10	3.37	2620	<2	0.02	33	0.106	31	0.76	15	17	279	<5	0.24	<10	<10	163	<10	82	5
122648	0.8	1.84	32	148	<0.5	<5	5.97	<1	16	9	30	3.68	<1	0.32	14	1.03	2826	<2	0.03	4	0.168	19	0.35	7	3	149	<5	0.04	<10	<10	33	<10	62	1
122649	1.0	2.15	89	197	<0.5	<5	5.72	2	18	7	41	4.86	<1	0.33	12	1.14	3102	<2	0.03	3	0.165	27	1.21	9	2	219	<5	0.03	<10	<10	41	<10	89	2
122650	0.9	2.41	155	174	<0.5	<5	4.10	3	17	17	30	5.59	<1	0.34	10	1.30	2638	<2	0.03	4	0.185	32	1.47	11	2	141	<5	0.01	<10	<10	45	<10	106	3
122651	1.0	1.60	2393	160	<0.5	<5	7.32	55	15	25	31	4.03	<1	0.32	10	0.83	2926	<2	0.03	3	0.159	23	1.58	11	2	397	<5	0.06	<10	<10	32	<10	80	2
122652	0.9	1.60	6107	170	<0.5	<5	3.73	144	17	14	36	4.53	<1	0.33	12	0.94	1886	<2	0.03	3	0.166	35	2.10	14	2	147	<5	0.04	<10	<10	31	<10	107	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Quality Assaying for over 25 Years

Assay Certificate

8V-3634-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth /shipment33-b**
Attn: **Sue Deane**

Oct-24-08

We hereby certify the following assay of 22 core samples submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130490	0.03	0.02	1.2
130491	0.06		1.0
130492	0.01		1.2
130493	0.03		1.1
130494	0.07		0.8
130495	<0.01		0.6
130496	0.01		0.6
130497	0.02		1.0
130498	0.04		1.1
130499	0.02	0.03	<0.1
130500	<0.01		<0.1
130501	0.49		2.2
130502	0.28		1.2
130503	0.11		1.2
130504	0.01		0.7
130505	0.01		<0.1
130506	0.01		<0.1
130507	0.01		0.4
130508	0.01		0.3
130509	0.02	0.02	0.5
130509A	0.01		0.4
130510	0.03		0.6
*0211	2.17		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3634-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth /shipment33-b**
Attn: **Sue Deane**

Oct-24-08

We hereby certify the following assay of 22 core samples submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130511	0.02	0.02	0.4
130512	0.03		0.4
130513	0.02		0.4
130514	0.02		0.9
130515	0.01		0.8
130516	0.02		0.6
130517	0.01		0.4
130518	0.05		1.6
130519	0.03		0.9
130520	0.02	0.01	0.5
130521	0.02		0.3
130522	0.01		0.4
130523	0.02		0.4
130524	0.01		0.2
130525	<0.01		<0.1
130526	0.01		0.2
130527	0.01		0.3
130528	<0.01		0.3
130529	0.03		0.6
130530	0.02	0.01	0.8
130531	0.02		0.8
130532	0.02		0.6
*0211	2.16		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3634-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth /shipment33-b**
Attn: **Sue Deane**

Oct-24-08

We hereby certify the following assay of 22 core samples submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130533	0.01	0.01	0.4
130534	0.02		0.2
130535	0.01		0.2
130536	0.01		0.3
130537	0.01		0.8
130538	0.01		0.8
130539	0.03		0.7
130540	<0.01		0.3
130541	0.02		0.6
130542	0.01	0.02	0.6
130543	0.03		1.1
130544	0.01		1.3
130545	0.08		1.6
130546	0.02		0.6
130547	0.07		1.1
130548	0.15		1.8
130549	0.06		1.4
130550	0.46		0.3
130551	0.02		0.8
130552	0.02	0.02	0.8
130553	0.05		1.4
130554	0.05		0.8
*0211	2.25		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3634-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth /shipment33-b**
Attn: **Sue Deane**

Oct-24-08

We hereby certify the following assay of 22 core samples submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130555	0.04	0.03	1.1
130556	0.05		0.7
130557	0.10		0.3
130558	0.23		2.1
130559	2.15		13.7
130560	0.86		3.5
130561	0.06		0.8
130562	0.08		0.9
130563	0.06		1.6
130564	0.07	0.05	0.6
130565	0.05		0.4
130566	0.06		0.4
130567	0.05		0.7
130568	0.04		0.6
130569	0.06		0.8
130570	1.03		3.9
130571	0.07		0.5
130572	0.04		0.2
130573	0.09		0.6
130574	0.03	0.02	0.5
130575	<0.01		<0.1
130576	0.03		0.2
*0211	2.13		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3634-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth /shipment33-b**
Attn: **Sue Deane**

Oct-24-08

We hereby certify the following assay of 22 core samples submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130577	0.02	<0.01	0.6
130578	0.02		1.3
130579	0.02		0.6
130580	0.01		0.1
130581	0.02		0.6
130582	0.02		1.1
130583	0.02		0.9
130584	0.09		1.2
130585	0.02		1.0
130586	0.08	0.08	1.8
130587	0.01		1.1
130588	0.02		0.9
130589	0.01		0.5
130590	<0.01		0.3
130591	0.01		0.5
130592	0.03		0.9
130593	0.07		1.0
130594	0.04		0.7
130595	0.03		0.9
130596	0.10	0.10	0.9
130597	0.05		0.4
130598	0.05		0.7
*0211	2.25		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3634-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth /shipment33-b**
Attn: **Sue Deane**

Oct-24-08

We hereby certify the following assay of 22 core samples submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
130599	0.03	0.03	0.6	
130600	0.12		>200	810.0
130601	0.03		0.9	
130602	0.12		3.3	
130603	0.02		0.7	
130604	0.04		0.5	
130605	0.04		0.5	
130606	0.03		1.8	
130607	0.06		1.1	
130608	0.05	0.05	1.0	
130609	0.02		0.4	
130610	0.06		0.7	
130611	0.03		0.9	
130612	0.02		0.5	
130613	0.01		0.5	
130614	0.02		0.4	
130615	0.09		1.3	
130616	0.19		0.9	
130617	0.03		1.3	
130618	0.01	0.01	0.9	
130619	0.02		0.9	
130620	0.05		1.9	
*0211	2.22			
*CCu-1c				131.0
*BLANK	<0.01			<0.1

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3634-RA7

Company: **Ascot Resources Ltd**
Project: **Dilworth /shipment33-b**
Attn: **Sue Deane**

Oct-24-08

We hereby certify the following assay of 22 core samples submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130621	0.03	0.04	1.0
130622	0.05		1.3
130623	<0.01		0.9
130624	<0.01		0.3
130625	<0.01		<0.1
130626	0.01		0.1
130627	0.03		0.3
130628	0.04		0.4
130629	0.01		0.4
130630	0.01	0.01	<0.1
130631	0.01		<0.1
130632	<0.01		<0.1
130633	0.01		<0.1
130634	<0.01		<0.1
130635	<0.01		<0.1
130636	<0.01		<0.1
130637	<0.01		<0.1
130638	<0.01		<0.1
130639	0.01		<0.1
130640	0.01	0.01	<0.1
130641	0.01		<0.1
130642	0.01		0.1
*0211	2.25		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3634-RA8

Company: **Ascot Resources Ltd**
Project: **Dilworth /shipment33-b**
Attn: **Sue Deane**

Oct-24-08

We hereby certify the following assay of 22 core samples
submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
130643	0.01	<0.01	0.3	
130644	0.01		0.4	
130645	0.03		0.6	
130646	0.01		0.8	
130647	0.01		1.7	
130648	0.05		2.8	
130649	0.03		1.5	
130650	0.12		>200	806.5
130651	0.01		2.7	
130652	0.05	0.03	1.3	
130653	0.01		1.9	
130654	0.06		2.5	
130655	0.05		1.9	
130656	0.04		1.4	
130657	0.03		0.6	
130658	0.04		0.9	
130659	0.03		1.2	
130660	0.03		0.8	
130661	0.04		0.9	
130662	0.02	0.03	1.0	
130663	0.18		1.6	
130664	0.01		0.9	
*0211	2.22			
*CCu-1c				129.7
*BLANK	<0.01			<0.1

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3634-RA9

Company: **Ascot Resources Ltd**
Project: **Dilworth /shipment33-b**
Attn: **Sue Deane**

Oct-24-08

We hereby certify the following assay of 22 core samples submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
130665	0.04	0.04	0.7
130666	0.01		0.6
130667	0.03		0.7
130668	0.02		0.9
130669	0.07		0.9
130670	0.01		0.5
130671	<0.01		<0.1
130672	0.01		0.2
130673	0.01		0.2
130674	0.01	0.03	0.3
130675	0.01		<0.1
130676	0.01		0.5
130677	0.02		0.5
130678	0.02		0.5
130679	0.01		0.5
130680	0.01		0.5
130681	0.01		0.3
130682	<0.01		0.5
130683	0.01		0.6
130684	0.01	0.02	0.4
130685	0.02		0.9
130686	0.06		1.5
*0211	2.25		
*BLANK	<0.01		

Certified by _____



Assayers Canada
 8282 Sherbrooke St.
 Vancouver, B.C.
 V5X 4R6
 Tel: (604) 327-3436
 Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3634-RA10

Company: **Ascot Resources Ltd**
 Project: **Dilworth /shipment33-b**
 Attn: **Sue Deane**

Oct-24-08

We hereby certify the following assay of 15 core samples submitted Oct-09-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
130687	0.29	0.28	4.4	
130688	0.13		2.3	
130689	0.16		4.1	
130690	0.03		0.8	
130691	0.03		0.9	
130692	0.03		1.0	
130693	0.01		0.9	
130694	0.04		1.2	
130695	0.01		0.3	
130696	0.04	0.04	1.5	
130697	0.03		0.8	
130698	0.01		0.4	
130699	<0.01		0.5	
130700	0.11		>200	809.0
130701	0.01		1.2	
*0211	2.15			
*CCu-1c				130.2
*BLANK	<0.01			<0.1

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3634RJ

Date : Oct-24-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth /shipment33-b

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130490	1.2	1.92	26	166	<0.5	<5	6.50	<1	13	15	85	4.79	<1	0.34	<10	0.97	2753	<2	0.03	1	1570	21	2.10	9	2	176	<5	0.01	<10	<10	37	<10	38	2
130491	1.0	2.15	45	182	<0.5	<5	6.00	1	23	15	58	5.54	<1	0.38	<10	1.13	2614	<2	0.03	2	1562	77	2.39	10	3	161	<5	0.01	<10	<10	43	<10	89	2
130492	1.2	2.48	47	169	<0.5	6	6.36	1	33	11	61	7.13	<1	0.35	<10	1.29	2757	<2	0.03	3	1942	27	3.64	13	5	221	<5	0.01	<10	<10	65	<10	146	3
130493	1.1	1.89	73	129	<0.5	5	6.15	1	22	10	42	6.54	<1	0.36	<10	0.91	2183	<2	0.02	3	1881	25	4.28	12	4	176	<5	0.01	<10	<10	49	<10	51	3
130494	0.8	2.54	28	144	<0.5	<5	5.15	<1	27	10	58	7.11	<1	0.34	<10	1.23	1980	<2	0.03	3	2010	31	3.36	14	6	151	<5	0.01	<10	<10	74	<10	72	3
130495	0.6	2.80	20	145	0.5	5	5.23	<1	26	11	43	7.87	<1	0.35	<10	1.43	2250	<2	0.03	3	2039	29	3.94	15	6	154	<5	0.01	<10	<10	87	<10	182	4
130496	0.6	1.75	37	45	0.5	6	3.01	<1	30	13	34	9.32	<1	0.47	<10	0.76	1409	<2	0.03	3	1765	31	>5.00	16	4	75	<5	0.01	<10	<10	47	<10	326	4
130497	1.0	2.41	44	85	<0.5	<5	4.62	1	29	19	51	7.07	<1	0.54	<10	1.09	2420	<2	0.06	3	1919	44	4.76	14	6	114	<5	0.03	<10	<10	71	<10	361	3
130498	1.1	2.55	43	70	<0.5	<5	4.73	1	30	17	62	7.83	<1	0.51	<10	1.16	2432	<2	0.05	3	1997	42	4.66	15	7	120	<5	0.06	<10	<10	80	<10	254	4
130499	<0.2	2.23	27	82	<0.5	<5	3.15	1	30	67	14	5.10	<1	0.11	27	2.10	1010	<2	0.06	25	3332	65	0.56	18	6	108	5	0.43	<10	<10	98	<10	148	25
130500	<0.2	0.13	10	22	<0.5	13	>15.00	<1	1	3	2	0.14	<1	0.04	<10	2.02	71	<2	0.01	1	116	<2	0.11	<5	<1	3575	<5	<0.01	<10	26	4	<10	5	<1
130501	2.2	1.91	1652	137	<0.5	<5	4.54	39	21	11	24	5.61	<1	0.38	<10	0.83	2162	<2	0.01	2	1578	49	2.50	17	2	134	<5	0.11	<10	<10	43	<10	85	3
130502	1.2	2.14	1392	107	<0.5	<5	6.00	32	19	7	26	5.60	<1	0.38	<10	0.88	2110	<2	0.01	2	1446	42	2.08	15	2	194	<5	0.10	<10	<10	45	<10	91	3
130503	1.2	2.43	185	125	<0.5	<5	6.32	4	21	5	34	5.64	<1	0.41	<10	1.01	2257	<2	0.03	2	1616	40	1.50	14	3	160	<5	0.12	<10	<10	59	<10	130	3
130504	0.7	2.61	84	192	<0.5	<5	2.44	2	21	7	33	5.89	<1	0.38	<10	1.32	1956	<2	0.03	3	1762	35	0.74	14	3	64	<5	0.11	<10	<10	73	<10	114	3
130505	<0.2	2.96	17	208	<0.5	<5	2.69	<1	24	31	5	4.93	<1	0.13	12	2.38	1082	<2	0.03	4	1767	27	0.10	14	5	140	<5	0.22	<10	<10	85	<10	128	23
130506	<0.2	3.02	35	116	<0.5	<5	2.42	<1	25	32	12	5.38	<1	0.17	15	2.36	1367	<2	0.04	4	1856	30	0.10	14	6	110	<5	0.19	<10	<10	91	<10	139	19
130507	0.4	3.37	51	189	<0.5	<5	4.11	1	28	8	43	7.19	<1	0.27	<10	1.98	2446	<2	0.07	3	1731	40	0.53	16	6	105	<5	0.18	<10	<10	108	<10	136	5
130508	0.3	2.14	90	125	<0.5	<5	4.32	2	21	8	32	5.56	<1	0.32	<10	1.00	1707	<2	0.03	5	1803	30	1.32	14	4	129	<5	0.15	<10	<10	70	<10	101	4
130509	0.5	2.36	66	127	<0.5	<5	6.84	2	20	5	28	5.38	<1	0.33	<10	1.22	2029	<2	0.03	2	1652	34	1.16	12	4	222	<5	0.11	<10	<10	67	<10	108	4
130509A	0.4	2.36	72	144	<0.5	<5	3.87	2	17	5	28	5.39	<1	0.34	<10	1.23	1730	<2	0.02	2	1637	37	0.91	11	3	145	<5	0.03	<10	<10	62	<10	96	3
130510	0.6	2.32	51	112	<0.5	<5	7.42	4	19	5	26	4.72	<1	0.40	<10	1.11	1798	<2	0.01	2	1456	98	0.60	11	3	153	<5	0.11	<10	<10	47	<10	265	3
130511	0.4	2.45	51	119	<0.5	<5	7.67	2	18	10	21	4.98	<1	0.41	<10	1.11	1967	<2	0.02	2	1647	71	0.60	13	4	165	<5	0.15	<10	<10	50	<10	127	4
130512	0.4	2.08	80	121	<0.5	<5	4.33	2	21	10	38	4.85	<1	0.35	<10	1.04	1671	<2	0.02	3	1815	63	1.11	14	4	129	<5	0.12	<10	<10	63	<10	113	3
130513	0.4	1.99	67	123	<0.5	<5	5.20	2	19	6	27	5.15	<1	0.35	<10	0.94	1586	<2	0.02	2	1679	39	1.41	12	3	158	<5	0.12	<10	<10	55	<10	96	4
130514	0.9	2.50	74	104	<0.5	<5	5.58	2	20	10	30	5.46	<1	0.35	<10	1.27	1997	<2	0.01	2	1733	52	0.88	13	3	147	<5	0.11	<10	<10	58	<10	137	3
130515	0.8	2.55	50	111	<0.5	<5	5.51	2	21	5	33	5.31	<1	0.37	<10	1.30	2197	<2	0.02	2	1829	78	0.57	13	3	149	<5	0.12	<10	<10	63	<10	190	3
130516	0.6	2.27	51	88	<0.5	<5	5.47	1	20	8	26	5.38	<1	0.27	<10	1.26	2005	<2	0.03	2	1752	38	1.46	14	3	138	<5	0.12	<10	<10	67	<10	104	3
130517	0.4	1.70	35	99	<0.5	<5	4.95	<1	14	5	16	4.04	<1	0.29	<10	0.94	1526	<2	0.03	1	1820	24	1.30	11	2	129	<5	0.04	<10	<10	49	<10	44	2
130518	1.6	2.25	711	92	<0.5	<5	6.06	17	19	8	27	5.13	<1	0.36	<10	1.33	2034	<2	0.02	2	1790	68	1.41	16	2	143	<5	0.09	<10	<10	54	<10	164	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3634RJ

Date : Oct-24-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth /shipment33-b

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130519	0.9	1.99	105	99	<0.5	<5	6.34	2	18	5	18	5.73	<1	0.30	<10	1.12	1658	<2	0.03	1	1875	28	2.17	16	2	141	<5	0.11	<10	<10	55	<10	61	3
130520	0.5	2.13	54	110	<0.5	<5	6.30	1	22	5	24	6.25	<1	0.29	<10	1.21	1876	<2	0.03	1	1908	33	2.31	17	3	166	<5	0.12	<10	<10	60	<10	74	4
130521	0.3	2.01	57	127	<0.5	<5	4.98	1	19	5	23	6.38	<1	0.35	<10	0.97	1505	<2	0.03	1	1917	33	2.62	16	3	132	<5	0.15	<10	<10	57	<10	75	5
130522	0.4	2.03	54	104	<0.5	<5	6.23	3	17	4	21	5.17	<1	0.32	<10	1.00	1448	<2	0.03	1	1963	65	1.22	13	3	152	<5	0.10	<10	<10	45	<10	191	5
130523	0.4	2.25	64	111	<0.5	<5	3.90	1	20	5	30	5.77	<1	0.33	<10	1.19	1435	<2	0.02	2	1917	45	1.28	15	4	93	<5	0.11	<10	<10	62	<10	88	4
130524	0.2	1.48	66	111	<0.5	<5	3.72	2	35	4	34	4.18	<1	0.33	<10	0.59	1118	<2	0.03	8	2085	40	1.28	13	3	94	<5	0.12	<10	<10	41	<10	72	3
130525	<0.2	0.10	11	16	<0.5	14	>15.00	<1	1	2	1	0.13	<1	0.04	<10	1.99	73	<2	0.01	1	108	<2	0.12	<5	<1	5234	<5	<0.01	<10	25	3	<10	4	<1
130526	0.2	2.05	33	126	<0.5	<5	4.20	1	23	4	32	5.85	<1	0.34	<10	1.06	1519	<2	0.03	2	2074	38	1.83	15	3	104	<5	0.12	<10	<10	60	<10	141	4
130527	0.3	2.06	45	120	<0.5	<5	4.16	1	20	5	26	6.39	<1	0.34	<10	1.00	1565	<2	0.04	1	1957	53	2.32	14	3	101	<5	0.11	<10	<10	59	<10	108	4
130528	0.3	2.37	32	133	<0.5	<5	6.22	1	17	4	26	5.27	<1	0.31	<10	1.04	1744	<2	0.09	1	1938	44	1.46	12	3	145	<5	0.11	<10	<10	62	<10	164	3
130529	0.6	2.39	49	125	<0.5	<5	4.46	1	17	6	30	4.93	<1	0.40	<10	0.91	1652	<2	0.10	1	2031	39	1.35	11	3	107	<5	0.13	<10	<10	54	<10	100	3
130530	0.8	1.41	51	106	<0.5	<5	3.24	2	17	4	32	4.47	<1	0.37	<10	0.56	1256	<2	0.02	1	2096	40	2.12	12	2	82	<5	0.09	<10	<10	36	<10	190	3
130531	0.8	2.35	65	97	<0.5	<5	5.09	2	21	6	31	6.19	<1	0.36	<10	1.07	2096	<2	0.03	1	1916	50	1.63	15	2	128	<5	0.12	<10	<10	51	<10	199	3
130532	0.6	2.34	102	117	<0.5	<5	5.55	3	16	5	27	5.00	<1	0.54	<10	0.82	1902	<2	0.05	1	1933	56	1.12	13	2	114	<5	0.12	<10	<10	38	<10	181	3
130533	0.4	2.09	48	121	<0.5	<5	4.42	2	14	13	20	3.67	<1	0.61	<10	0.73	1593	<2	0.06	2	1854	24	0.42	9	3	74	<5	0.10	<10	<10	44	<10	148	2
130534	0.2	3.26	74	83	<0.5	<5	5.46	1	18	25	19	4.82	<1	0.49	<10	1.23	1903	<2	0.19	4	1759	11	1.35	13	6	117	<5	0.14	<10	<10	85	<10	90	3
130535	0.2	3.22	82	61	<0.5	<5	3.50	1	20	14	47	5.16	<1	0.16	<10	1.28	1283	<2	0.20	3	1666	14	1.37	13	6	92	<5	0.18	<10	<10	118	<10	112	7
130536	0.3	3.43	106	132	<0.5	<5	4.48	2	21	22	22	5.12	<1	0.50	10	1.47	1484	<2	0.22	7	2115	16	1.21	14	5	122	<5	0.21	<10	<10	94	<10	118	9
130537	0.8	3.41	83	150	<0.5	<5	5.44	2	20	7	31	5.39	<1	0.59	<10	1.34	1895	<2	0.19	2	1613	16	1.47	13	5	152	<5	0.14	<10	<10	88	<10	175	3
130538	0.8	2.32	158	90	<0.5	<5	5.72	3	20	5	32	5.44	<1	0.32	<10	1.14	1818	<2	0.09	2	1516	19	2.19	14	3	123	<5	0.10	<10	<10	64	<10	93	3
130539	0.7	1.78	338	86	<0.5	<5	4.27	8	19	5	30	4.79	<1	0.34	<10	1.06	1529	<2	0.02	2	1690	21	1.65	14	2	98	<5	0.10	<10	<10	52	<10	117	2
130540	0.3	1.70	82	80	<0.5	<5	5.36	1	16	5	20	4.42	<1	0.29	<10	1.00	1631	<2	0.02	1	1676	8	1.22	11	2	127	<5	0.09	<10	<10	49	<10	33	2
130541	0.6	1.99	103	84	<0.5	<5	6.53	2	16	6	24	4.78	<1	0.31	<10	1.21	1929	<2	0.02	2	1540	8	0.98	11	2	156	<5	0.09	<10	<10	53	<10	45	2
130542	0.6	1.66	123	85	<0.5	<5	5.04	3	17	7	23	5.03	<1	0.28	<10	0.85	1648	<2	0.02	2	1752	14	1.78	13	2	124	<5	0.08	<10	<10	43	<10	59	2
130543	1.1	1.81	190	93	<0.5	<5	3.98	5	23	6	37	5.98	<1	0.29	<10	0.96	1690	<2	0.01	2	1620	35	2.60	14	2	106	<5	0.04	<10	<10	50	<10	185	3
130544	1.3	2.16	147	109	<0.5	<5	5.94	4	23	8	26	5.03	<1	0.39	<10	1.16	2091	<2	0.01	4	1863	116	1.19	12	2	160	<5	0.03	<10	<10	51	<10	197	2
130545	1.6	1.57	167	131	<0.5	<5	4.52	5	18	8	33	5.05	<1	0.41	<10	0.71	1588	<2	0.01	2	1574	117	2.62	10	2	104	<5	0.02	<10	<10	31	<10	204	2
130546	0.6	2.09	75	90	0.7	5	5.18	1	18	8	34	5.73	<1	0.33	<10	1.21	1772	<2	0.02	2	1830	27	1.83	10	2	154	<5	0.01	<10	<10	48	<10	93	3
130547	1.1	1.50	599	82	<0.5	<5	5.91	15	17	7	27	5.33	<1	0.35	<10	0.78	1802	<2	0.01	2	1627	63	2.87	12	2	159	<5	0.02	<10	<10	31	<10	140	2
130548	1.8	0.98	1129	103	0.5	<5	4.76	28	17	9	69	4.50	<1	0.40	<10	0.34	1342	<2	0.02	3	1404	53	3.41	16	2	133	<5	0.01	<10	<10	22	<10	139	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3634RJ

Date : Oct-24-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth /shipment33-b

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130549	1.4	1.96	660	78	<0.5	<5	5.91	16	24	6	38	6.77	<1	0.30	<10	1.02	2075	<2	0.01	3	1731	62	2.80	18	2	148	<5	0.07	<10	<10	40	<10	97	3
130550	0.3	1.14	7019	23	<0.5	21	7.07	172	182	14	72	4.28	<1	0.05	12	0.28	790	15	0.09	34	1544	14	1.42	12	1	93	<5	0.07	<10	<10	40	<10	98	11
130551	0.8	2.15	90	78	<0.5	<5	5.02	2	21	7	25	6.36	<1	0.27	<10	1.14	2090	<2	0.02	2	1607	26	2.09	13	2	134	<5	0.08	<10	<10	51	<10	99	3
130552	0.8	2.28	95	70	<0.5	<5	4.85	2	21	6	23	6.37	<1	0.25	<10	1.25	2269	<2	0.02	2	1691	28	1.62	14	2	136	<5	0.08	<10	<10	53	<10	143	3
130553	1.4	2.01	329	104	<0.5	<5	4.77	9	23	7	35	5.65	<1	0.40	<10	0.99	1921	<2	0.01	3	1766	85	2.04	16	2	133	<5	0.07	<10	<10	37	<10	284	2
130554	0.8	1.79	658	94	<0.5	<5	4.56	16	16	7	21	5.02	<1	0.34	<10	0.81	1807	<2	0.01	1	1655	25	1.41	13	2	121	<5	0.07	<10	<10	28	<10	88	2
130555	1.1	1.58	257	92	<0.5	<5	3.66	6	19	7	39	5.11	<1	0.35	<10	0.70	1672	<2	0.01	3	1525	25	2.32	<5	2	102	<5	0.03	<10	10	25	<10	119	2
130556	0.7	1.62	285	115	<0.5	<5	4.43	8	17	5	32	4.89	<1	0.43	<10	0.68	1749	<2	0.02	3	1767	66	2.23	<5	2	124	<5	0.05	<10	10	34	<10	219	2
130557	0.3	1.45	94	129	<0.5	<5	4.00	2	16	9	26	4.27	<1	0.41	<10	0.63	1437	<2	0.01	3	1592	19	2.04	<5	3	95	<5	0.03	<10	<10	35	<10	94	2
130558	2.1	1.05	270	110	<0.5	<5	8.67	7	19	12	58	4.65	<1	0.37	<10	0.32	2746	<2	0.02	4	1202	54	3.54	<5	4	215	<5	0.05	<10	12	48	<10	172	2
130559	13.7	0.59	4929	90	<0.5	<5	6.72	122	17	15	109	3.92	<1	0.31	<10	0.18	2268	<2	0.01	3	978	318	3.48	11	2	196	<5	0.01	<10	10	16	<10	599	2
130560	3.5	0.98	1585	116	<0.5	<5	8.52	37	15	6	42	3.26	<1	0.37	<10	0.37	2213	<2	0.01	3	1248	61	1.78	<5	2	288	<5	0.02	<10	<10	23	<10	126	1
130561	0.8	1.63	213	103	<0.5	<5	5.99	5	16	3	30	4.31	<1	0.35	<10	0.81	1906	<2	0.01	3	1621	24	1.23	<5	2	217	<5	0.04	<10	<10	40	<10	77	2
130562	0.9	1.72	129	105	<0.5	<5	6.72	4	20	3	32	4.86	<1	0.32	<10	0.87	1847	<2	0.01	3	1738	32	1.40	<5	2	237	<5	0.03	<10	<10	46	<10	84	2
130563	1.6	1.90	88	109	<0.5	<5	6.03	5	27	2	56	5.88	<1	0.34	<10	0.98	1699	<2	0.01	4	2043	68	2.23	<5	3	184	<5	0.08	<10	<10	59	<10	93	3
130564	0.6	1.54	152	81	<0.5	<5	7.95	4	15	7	25	4.67	<1	0.27	<10	0.83	1949	<2	<0.01	3	1283	38	1.60	<5	2	252	<5	0.05	<10	<10	34	<10	123	2
130565	0.4	1.93	86	89	<0.5	<5	6.85	2	22	5	28	4.45	<1	0.27	<10	1.32	2155	<2	0.01	4	1242	22	0.62	<5	2	214	<5	0.07	<10	<10	43	<10	105	2
130566	0.4	1.15	149	103	<0.5	<5	6.53	4	14	5	25	3.12	<1	0.32	<10	0.65	1751	<2	0.01	3	1363	29	1.18	<5	1	245	<5	0.04	<10	<10	19	<10	175	1
130567	0.7	1.45	749	83	<0.5	<5	7.93	18	17	6	23	4.71	<1	0.26	<10	0.87	2280	<2	0.01	3	1156	23	2.14	<5	1	247	<5	0.02	<10	10	32	<10	109	2
130568	0.6	1.58	102	89	<0.5	<5	6.29	2	16	7	19	4.77	<1	0.26	<10	0.89	2087	<2	0.01	3	1316	12	1.82	<5	1	202	<5	0.04	<10	11	33	<10	105	2
130569	0.8	1.16	106	103	<0.5	<5	5.02	2	15	6	25	4.26	<1	0.29	<10	0.54	1738	<2	0.01	3	1413	15	2.30	<5	1	159	<5	0.03	<10	<10	27	<10	102	2
130570	3.9	0.61	929	112	<0.5	<5	4.66	23	13	11	31	2.88	<1	0.32	<10	0.20	1301	<2	0.01	3	1293	70	2.47	<5	1	136	<5	0.01	<10	<10	13	<10	267	1
130571	0.5	0.82	401	114	<0.5	<5	5.77	9	12	6	23	2.53	<1	0.35	<10	0.31	1476	<2	0.01	2	1319	18	1.49	<5	2	153	<5	0.01	<10	<10	17	<10	75	1
130572	0.2	2.90	25	235	<0.5	<5	3.42	<1	20	11	40	4.87	<1	0.71	<10	0.96	1821	<2	0.19	4	1273	12	0.41	<5	4	100	<5	0.08	<10	<10	75	<10	137	3
130573	0.6	2.25	46	176	<0.5	<5	2.55	2	19	7	55	5.08	<1	0.54	<10	0.74	1437	<2	0.08	3	1424	61	0.66	<5	3	60	<5	0.04	<10	<10	56	<10	208	2
130574	0.5	2.49	61	127	<0.5	<5	4.05	1	20	3	45	6.27	<1	0.32	<10	1.13	1985	<2	0.04	3	1422	11	0.35	<5	3	104	<5	0.03	<10	14	71	<10	125	3
130575	<0.2	0.12	<5	17	<0.5	8	>15.00	<1	1	2	2	0.15	<1	0.04	<10	4.10	96	<2	0.01	1	141	<2	0.05	<5	<1	4285	<5	<0.01	<10	<10	3	<10	5	<1
130576	0.2	1.97	30	121	<0.5	<5	5.01	<1	17	3	30	4.95	<1	0.30	<10	0.94	1871	<2	0.02	3	1585	7	0.29	<5	2	147	<5	0.03	<10	<10	53	<10	85	2
130577	0.6	2.48	39	154	<0.5	<5	4.40	<1	19	3	45	5.90	<1	0.39	<10	1.06	1774	<2	0.02	2	1541	8	0.28	11	2	120	<5	0.04	<10	<10	54	<10	76	3
130578	1.3	4.08	59	253	<0.5	7	7.89	1	40	6	74	9.24	<1	0.69	14	1.80	3137	<2	0.05	6	3030	35	0.87	17	5	214	<5	0.07	<10	<10	104	<10	299	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3634RJ

Date : Oct-24-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth /shipment33-b

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130579	0.6	2.19	22	105	2.6	5	5.73	<1	22	6	35	5.30	<1	0.42	<10	1.13	2130	<2	0.02	3	1609	24	0.61	10	4	129	<5	0.01	<10	<10	57	<10	127	2
130580	<0.2	2.46	27	145	<0.5	<5	6.07	<1	16	6	13	4.42	<1	0.44	<10	1.11	1526	<2	0.09	1	1497	26	0.26	9	4	110	<5	0.08	<10	<10	57	<10	106	2
130581	0.6	2.25	63	112	<0.5	<5	6.30	1	17	5	23	5.48	<1	0.33	<10	1.04	1905	<2	0.02	2	1605	40	0.60	10	2	135	<5	0.05	<10	<10	48	<10	106	2
130582	1.1	2.05	96	100	<0.5	<5	6.93	3	15	9	34	4.81	<1	0.31	<10	1.02	2049	<2	0.01	2	1388	73	0.46	9	2	287	<5	0.03	<10	<10	40	<10	206	2
130583	0.9	2.17	40	120	<0.5	<5	5.23	<1	19	5	48	5.40	<1	0.34	10	1.04	1598	<2	0.02	2	1670	11	0.62	10	2	121	<5	0.05	<10	<10	49	<10	80	2
130584	1.2	2.03	102	123	<0.5	<5	2.56	2	22	6	52	5.40	<1	0.34	<10	1.03	1275	<2	0.01	3	1637	18	1.04	11	2	76	<5	0.03	<10	<10	42	<10	86	2
130585	1.0	2.35	95	120	<0.5	<5	3.57	2	21	3	36	5.49	<1	0.36	<10	1.26	1576	<2	0.01	2	1651	15	0.45	11	2	99	<5	0.04	<10	<10	48	<10	149	2
130586	1.8	2.15	441	109	<0.5	<5	4.67	10	18	20	51	5.71	<1	0.30	<10	1.38	1566	<2	0.01	5	1858	24	1.37	15	4	143	<5	0.06	<10	<10	45	<10	109	3
130587	1.1	2.61	62	120	<0.5	<5	4.42	1	21	26	53	5.91	<1	0.30	<10	1.98	1491	<2	0.01	7	2138	8	0.68	14	5	153	<5	0.09	<10	<10	67	<10	96	3
130588	0.9	2.18	182	121	<0.5	<5	4.83	4	18	21	56	5.24	<1	0.33	<10	1.48	1291	<2	0.01	5	2254	10	1.17	13	4	142	<5	0.04	<10	<10	47	<10	95	3
130589	0.5	2.47	45	115	<0.5	<5	4.28	1	17	24	44	5.36	<1	0.25	<10	1.71	1514	<2	0.01	6	1950	14	0.19	11	5	131	<5	0.06	<10	<10	61	<10	106	3
130590	0.3	2.70	45	144	<0.5	<5	3.61	1	15	23	41	5.64	<1	0.27	<10	1.88	1438	<2	0.01	5	2037	10	0.06	10	5	129	<5	0.02	<10	<10	61	<10	96	3
130591	0.5	2.67	42	127	0.8	5	4.72	1	19	30	43	5.79	<1	0.30	12	1.82	1467	<2	0.02	8	2159	48	0.49	9	5	259	<5	0.01	<10	<10	61	<10	152	3
130592	0.9	1.97	73	77	0.6	6	11.44	2	16	33	33	4.63	<1	0.20	10	1.49	3163	<2	0.02	6	1520	220	0.97	8	8	350	<5	<0.01	<10	<10	87	<10	142	2
130593	1.0	2.93	88	76	0.7	5	7.13	4	27	56	84	6.89	<1	0.19	<10	2.58	2190	<2	0.01	12	1768	69	1.59	13	11	229	<5	0.01	<10	<10	154	<10	387	3
130594	0.7	2.87	71	80	0.7	5	5.01	1	30	53	84	6.94	<1	0.19	<10	2.78	1694	<2	0.02	12	2051	42	1.92	13	11	156	<5	0.01	<10	<10	172	<10	123	3
130595	0.9	2.88	58	66	0.7	5	4.98	1	27	51	83	6.75	<1	0.14	<10	2.73	1703	<2	0.01	11	1904	63	1.29	12	12	162	<5	0.01	<10	<10	175	<10	139	3
130596	0.9	2.68	84	68	0.7	5	6.51	5	28	47	102	6.81	<1	0.13	<10	2.37	1839	<2	0.02	11	1806	279	1.85	12	11	205	<5	0.01	<10	<10	165	11	582	3
130597	0.4	2.96	85	75	0.9	5	6.33	2	28	66	77	6.41	<1	0.14	<10	2.88	2238	<2	0.01	14	1847	45	1.29	12	14	228	<5	0.01	<10	<10	186	<10	154	3
130598	0.7	2.90	149	80	0.9	6	8.04	3	28	68	61	6.65	<1	0.20	<10	2.57	2435	<2	0.01	14	1819	33	1.64	13	13	275	<5	0.01	<10	<10	158	<10	115	3
130599	0.6	2.76	97	90	<0.5	6	10.19	2	30	66	35	6.51	<1	0.20	<10	2.15	3345	<2	0.01	16	1860	12	1.47	<5	13	274	<5	<0.01	<10	18	160	<10	80	3
130600	>200.0	0.57	607	187	<0.5	115	0.55	23	7	19	7290	2.25	7	0.15	<10	0.55	287	585	0.02	5	419	924	1.18	1762	1	73	<5	0.05	<10	<10	18	<10	994	2
130601	0.9	3.26	127	82	<0.5	6	5.90	2	28	80	50	6.90	<1	0.13	<10	2.94	2563	<2	0.01	15	1807	31	0.96	<5	14	161	<5	0.01	<10	14	190	<10	101	3
130602	3.3	2.47	610	73	<0.5	6	6.67	21	29	35	123	6.60	<1	0.21	<10	2.04	2337	<2	0.01	15	1643	964	2.70	<5	7	177	<5	0.01	<10	17	90	16	911	3
130603	0.7	3.50	110	83	<0.5	<5	5.17	4	30	53	105	6.72	<1	0.18	<10	3.19	2047	<2	0.01	14	1812	41	0.40	<5	10	177	<5	0.03	<10	13	145	<10	303	3
130604	0.5	2.99	104	146	<0.5	<5	5.87	2	28	44	92	6.05	<1	0.31	<10	2.47	1872	<2	0.01	13	1707	28	0.78	<5	10	209	<5	0.03	<10	<10	122	<10	130	3
130605	0.5	2.90	94	215	<0.5	<5	5.22	2	31	51	94	6.30	<1	0.50	<10	2.26	1871	<2	0.02	14	2025	20	1.26	<5	12	205	<5	0.03	<10	12	142	<10	111	3
130606	1.8	2.52	117	89	<0.5	<5	4.38	8	37	47	126	6.59	1	0.17	<10	2.39	1944	<2	0.03	15	1924	564	2.60	<5	16	191	<5	0.13	<10	10	227	18	1007	5
130607	1.1	2.20	88	88	<0.5	<5	4.10	2	33	42	93	6.29	<1	0.23	<10	1.79	1536	<2	0.06	15	1733	31	4.03	<5	11	135	<5	0.15	<10	<10	155	<10	110	5
130608	1.0	2.88	92	140	<0.5	<5	6.09	2	30	61	91	6.55	1	0.32	<10	2.41	1927	<2	0.06	16	1733	62	2.30	<5	13	180	<5	0.05	<10	12	161	<10	139	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3634RJ**

Date : Oct-24-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth /shipment33-b

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130609	0.4	2.42	93	82	<0.5	<5	6.03	2	30	38	64	5.58	<1	0.21	<10	2.04	1603	<2	0.01	14	1762	12	1.05	<5	8	170	<5	0.02	<10	<10	100	<10	83	3
130610	0.7	2.06	201	182	<0.5	<5	6.85	5	27	39	59	5.49	<1	0.24	<10	1.66	1845	<2	0.01	15	1640	30	2.06	<5	8	208	<5	0.04	<10	<10	75	<10	159	3
130611	0.9	2.72	52	73	<0.5	<5	7.57	2	33	48	78	6.50	<1	0.17	<10	2.27	2117	<2	0.01	17	1666	195	1.59	<5	10	212	<5	0.08	<10	11	110	<10	208	3
130612	0.5	3.43	39	57	<0.5	<5	5.60	1	32	77	74	7.18	1	0.09	<10	3.27	1795	<2	0.01	18	1739	104	1.04	<5	16	161	<5	0.08	<10	11	204	<10	167	4
130613	0.5	3.07	53	63	<0.5	<5	6.27	1	31	73	72	6.67	1	0.10	<10	2.96	2019	<2	0.01	16	1758	69	1.01	<5	14	179	<5	0.06	<10	12	180	<10	121	4
130614	0.4	3.22	53	59	<0.5	<5	5.15	1	32	67	70	6.74	<1	0.11	<10	2.96	1919	<2	0.01	17	1857	13	0.18	<5	15	153	<5	0.06	<10	12	187	<10	116	3
130615	1.3	2.78	1395	116	<0.5	<5	6.60	46	29	77	99	6.10	<1	0.20	10	2.60	2227	<2	0.05	30	1925	194	0.71	<5	13	165	<5	0.12	<10	10	161	28	1766	6
130616	0.9	1.92	4087	145	<0.5	<5	10.03	97	25	44	44	4.89	<1	0.43	<10	1.41	3051	<2	0.02	15	1387	148	1.58	<5	11	300	<5	0.04	<10	11	103	<10	216	2
130617	1.3	2.73	148	94	<0.5	<5	6.44	5	37	122	100	5.96	1	0.42	<10	2.11	1844	3	0.11	28	2032	99	3.32	<5	18	190	<5	0.12	<10	<10	209	<10	224	5
130618	0.9	2.46	81	74	<0.5	<5	7.46	2	41	214	148	5.55	1	0.21	<10	2.18	1569	<2	0.06	44	2129	48	1.80	<5	12	163	<5	0.09	<10	<10	164	<10	142	4
130619	0.9	2.83	50	72	<0.5	<5	8.53	1	41	271	72	6.37	1	0.14	<10	3.08	2244	2	0.03	42	1812	61	1.98	<5	24	237	<5	0.06	<10	11	224	<10	155	4
130620	1.9	2.39	178	62	<0.5	<5	10.01	5	31	199	65	6.68	<1	0.23	<10	2.46	2190	<2	0.03	36	1666	65	3.59	<5	17	231	<5	0.07	<10	15	153	<10	259	4
130621	1.0	2.12	244	43	<0.5	<5	12.69	6	30	172	77	5.21	<1	0.15	<10	2.31	2209	<2	0.01	35	1511	32	2.46	<5	13	348	<5	0.05	<10	<10	105	<10	103	3
130622	1.3	2.36	308	45	<0.5	<5	13.00	7	35	201	84	6.08	<1	0.15	<10	2.65	2119	<2	0.01	41	1839	40	3.14	<5	14	303	<5	0.10	<10	14	110	<10	104	4
130623	0.9	2.65	294	35	<0.5	<5	12.35	6	34	256	86	6.34	<1	0.05	<10	2.98	2230	<2	0.01	38	1660	6	2.62	<5	25	293	<5	0.11	<10	12	203	<10	85	4
130624	0.3	2.89	38	35	<0.5	<5	11.08	<1	32	269	87	5.86	1	0.03	<10	3.48	1802	<2	0.01	36	1514	3	1.71	<5	29	277	<5	0.11	<10	<10	230	<10	72	4
130625	<0.2	0.09	<5	<10	<0.5	7	>15.00	<1	1	7	3	0.17	1	0.01	<10	6.55	172	<2	0.01	1	230	<2	0.05	<5	1	2628	<5	<0.01	<10	<10	5	<10	4	<1
130626	<0.2	2.96	31	34	<0.5	<5	10.23	<1	35	280	87	6.26	1	0.02	<10	3.55	1798	<2	0.01	40	1629	5	2.06	<5	31	277	<5	0.12	<10	<10	241	<10	78	5
130627	0.3	2.33	259	41	<0.5	<5	10.83	6	34	256	90	5.76	1	0.04	<10	3.06	1894	<2	0.01	38	1617	7	2.94	<5	26	323	<5	0.12	<10	<10	213	<10	66	4
130628	0.4	2.87	320	37	<0.5	<5	12.45	7	32	249	72	5.78	<1	0.04	<10	3.51	2448	<2	0.01	37	1644	21	1.76	<5	26	431	<5	0.07	<10	11	204	<10	104	3
130629	0.4	2.81	50	57	<0.5	<5	8.86	2	38	297	103	6.21	<1	0.03	<10	3.62	1929	<2	0.01	43	1774	50	2.13	<5	31	312	<5	0.11	<10	<10	249	<10	229	5
130630	<0.2	2.48	31	41	<0.5	<5	10.53	<1	34	272	79	6.22	1	0.02	<10	3.10	1965	2	0.01	38	1536	5	2.47	<5	29	358	<5	0.11	<10	<10	223	<10	74	6
130631	<0.2	3.03	36	57	<0.5	<5	9.22	<1	41	323	107	6.99	1	0.03	<10	3.90	1951	<2	0.01	48	1759	4	2.20	<5	32	327	<5	0.14	<10	<10	269	<10	85	7
130632	<0.2	2.72	26	42	<0.5	<5	10.65	<1	36	294	87	6.29	1	0.02	<10	3.39	1925	<2	0.01	42	1563	3	1.82	<5	30	305	<5	0.12	<10	<10	242	<10	75	5
130633	<0.2	2.79	23	35	<0.5	<5	8.94	<1	34	268	86	6.11	<1	0.02	<10	3.57	2041	<2	0.02	40	1676	9	1.64	<5	27	273	<5	0.12	<10	10	222	<10	80	5
130634	<0.2	2.66	20	35	<0.5	<5	11.90	1	35	273	89	5.85	<1	0.02	<10	3.41	2121	<2	0.02	40	1570	49	1.58	<5	27	375	<5	0.11	<10	<10	229	<10	123	5
130635	<0.2	2.64	26	36	<0.5	<5	10.74	<1	32	257	81	5.71	<1	0.01	<10	3.36	2270	<2	0.02	36	1567	4	1.37	<5	26	347	<5	0.10	<10	<10	216	<10	70	4
130636	<0.2	2.46	22	41	<0.5	<5	11.52	<1	32	244	84	5.75	<1	0.01	<10	3.05	2218	<2	0.01	36	1550	3	1.41	<5	26	374	<5	0.10	<10	<10	210	<10	67	4
130637	<0.2	2.30	23	50	<0.5	<5	10.55	<1	34	271	93	5.57	<1	0.02	<10	2.80	2087	<2	0.01	39	1629	4	1.74	<5	30	353	<5	0.12	<10	<10	229	<10	79	5
130638	<0.2	2.63	47	34	<0.5	<5	14.53	1	27	201	45	5.55	<1	0.02	<10	3.07	2576	<2	0.01	29	1363	5	1.83	<5	24	540	<5	0.08	<10	14	175	<10	106	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3634RJ**

Date : Oct-24-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth /shipment33-b

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130639	<0.2	3.18	31	31	<0.5	<5	7.41	<1	35	286	89	5.98	1	0.01	<10	4.00	1630	<2	0.01	39	1715	7	0.96	<5	32	236	<5	0.12	<10	<10	236	<10	85	5
130640	<0.2	2.82	31	37	<0.5	<5	9.40	<1	35	269	87	5.71	1	0.01	<10	3.31	1680	<2	0.01	40	1584	2	1.10	<5	31	316	<5	0.10	<10	<10	231	<10	71	4
130641	<0.2	2.96	28	58	<0.5	<5	8.95	<1	34	272	88	6.07	1	0.01	<10	3.59	1737	<2	0.01	38	1588	18	1.22	<5	31	295	<5	0.10	<10	<10	229	<10	91	4
130642	<0.2	3.00	61	39	<0.5	<5	8.08	1	37	289	95	5.99	1	0.02	<10	3.71	1713	<2	0.01	40	1791	24	1.63	<5	30	244	<5	0.11	<10	<10	245	<10	143	4
130643	0.3	3.42	47	45	<0.5	<5	7.56	1	37	285	89	6.05	1	0.02	<10	4.30	1827	<2	0.01	41	1786	15	1.36	<5	32	274	<5	0.12	<10	<10	235	<10	111	6
130644	0.4	3.58	55	31	<0.5	<5	8.87	1	36	288	90	6.66	<1	0.02	<10	4.29	2085	<2	0.01	41	1777	36	1.39	<5	33	268	<5	0.14	<10	<10	242	<10	105	7
130645	0.6	2.90	139	35	<0.5	<5	11.02	3	36	270	89	5.72	<1	0.03	<10	3.24	2307	<2	0.01	40	1921	15	1.45	<5	26	326	<5	0.13	<10	10	217	<10	128	4
130646	0.8	3.42	71	31	<0.5	<5	8.67	1	37	286	90	6.32	1	0.03	<10	4.00	2235	<2	0.01	43	1844	12	1.67	<5	28	285	<5	0.11	<10	11	234	<10	97	4
130647	1.7	3.00	93	51	<0.5	<5	9.63	2	39	263	91	6.25	<1	0.07	<10	3.22	2352	<2	0.02	45	1879	16	2.25	<5	21	288	<5	0.10	<10	13	183	<10	76	4
130648	2.8	2.95	126	208	<0.5	<5	5.53	5	33	94	93	6.54	<1	0.42	<10	2.20	1700	<2	0.06	20	2139	39	2.57	<5	13	146	<5	0.10	<10	13	128	<10	407	4
130649	1.5	3.09	82	119	<0.5	<5	5.82	2	30	45	78	7.06	<1	0.24	<10	2.24	1897	<2	0.03	14	2258	42	1.26	<5	8	154	<5	0.04	<10	14	104	<10	149	4
130650	>200.0	0.60	616	196	<0.5	112	0.58	23	8	19	7449	2.36	7	0.15	<10	0.58	294	589	0.03	5	422	941	1.19	1819	2	75	<5	0.06	<10	<10	19	<10	1009	2
130651	2.7	2.57	139	106	<0.5	5	5.97	4	26	27	78	6.51	<1	0.21	<10	1.94	1821	<2	0.01	12	2034	60	1.86	<5	6	161	<5	0.02	<10	12	74	<10	191	3
130652	1.3	2.34	80	107	<0.5	<5	6.10	2	24	23	63	5.76	<1	0.19	<10	1.63	1723	<2	0.01	10	1965	13	1.38	<5	6	167	<5	0.01	<10	10	60	<10	89	3
130653	1.9	2.13	116	94	<0.5	5	7.20	2	25	22	71	5.94	<1	0.21	<10	1.42	2166	<2	0.01	11	2102	20	2.17	<5	6	177	<5	0.02	<10	12	52	<10	83	3
130654	2.5	2.09	174	87	<0.5	5	7.82	4	28	24	77	6.29	<1	0.20	<10	1.48	2257	<2	0.01	12	2131	27	2.87	<5	6	214	<5	0.01	<10	13	55	<10	131	3
130655	1.9	2.38	130	104	<0.5	6	6.60	3	28	26	68	6.60	<1	0.25	<10	1.68	1928	<2	0.01	12	2033	33	2.47	<5	7	194	<5	0.01	<10	16	64	<10	122	3
130656	1.4	2.53	150	86	<0.5	<5	7.37	3	25	34	72	6.07	<1	0.21	<10	1.80	2032	<2	0.01	11	2113	13	1.32	<5	6	210	<5	0.01	<10	16	66	<10	107	3
130657	0.6	2.28	60	93	<0.5	5	5.98	2	19	19	45	5.38	<1	0.23	<10	1.29	2223	<2	0.01	7	1915	35	0.65	<5	5	145	<5	0.01	<10	12	43	<10	128	2
130658	0.9	2.51	141	95	<0.5	6	7.08	3	21	35	55	5.45	<1	0.23	<10	1.56	2547	<2	0.01	9	1985	18	0.45	<5	6	151	<5	0.01	<10	11	67	<10	114	2
130659	1.2	2.86	68	86	<0.5	6	6.62	1	27	33	78	6.53	<1	0.20	<10	1.64	2364	<2	0.01	13	2073	9	0.43	<5	7	144	<5	0.01	<10	12	77	<10	114	3
130660	0.8	2.40	89	116	<0.5	<5	6.50	2	24	31	59	5.41	<1	0.29	<10	1.19	2183	<2	0.01	10	2056	9	0.24	<5	7	137	<5	0.02	<10	10	62	<10	108	2
130661	0.9	2.50	27	153	<0.5	<5	4.68	<1	20	33	77	5.02	<1	0.56	<10	0.96	1780	3	0.06	7	1933	15	0.55	<5	9	69	<5	0.08	<10	<10	77	<10	111	4
130662	1.0	2.37	58	152	<0.5	<5	4.66	2	26	11	74	5.62	<1	0.45	<10	0.90	1898	<2	0.03	7	1625	62	0.61	<5	5	90	<5	0.04	<10	10	59	<10	168	3
130663	1.6	2.11	86	139	<0.5	<5	6.16	2	22	6	114	5.23	<1	0.36	<10	0.76	1918	<2	0.03	4	1536	60	1.08	<5	3	118	<5	0.03	<10	10	47	<10	119	2
130664	0.9	2.17	34	116	<0.5	5	4.70	1	19	4	66	5.45	<1	0.26	<10	0.85	1866	<2	0.01	3	1573	14	0.34	<5	3	89	<5	<0.01	<10	10	44	<10	99	2
130665	0.7	2.68	79	144	<0.5	5	6.14	1	18	3	38	6.32	<1	0.34	<10	0.94	2053	<2	0.02	2	1518	16	0.35	11	3	110	<5	0.01	<10	<10	50	<10	109	3
130666	0.6	2.84	26	142	<0.5	5	5.53	<1	20	5	35	6.97	<1	0.34	<10	1.07	2071	<2	0.02	1	1709	21	0.28	12	3	100	<5	0.02	<10	<10	52	<10	128	3
130667	0.7	1.90	28	132	<0.5	<5	5.77	<1	15	17	29	4.73	<1	0.34	<10	0.62	1539	<2	0.02	2	1516	16	0.39	8	2	102	<5	0.02	<10	<10	28	<10	88	2
130668	0.9	2.42	53	138	<0.5	<5	5.60	1	21	5	32	5.92	<1	0.36	<10	0.85	1931	3	0.04	2	1648	24	0.69	12	3	95	<5	0.05	<10	<10	42	<10	97	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3634RJ

Date : Oct-24-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth /shipment33-b

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130669	0.9	4.18	116	267	<0.5	<5	6.89	2	20	11	36	5.39	<1	1.05	<10	1.01	2140	<2	0.20	3	1616	16	0.28	13	5	117	<5	0.12	<10	<10	81	<10	94	3
130670	0.5	4.82	24	112	<0.5	<5	4.17	<1	17	30	76	4.55	<1	0.33	<10	1.00	846	<2	0.41	3	1600	9	0.31	13	5	124	<5	0.19	<10	<10	95	<10	122	5
130671	<0.2	6.21	30	247	<0.5	<5	5.59	<1	20	16	26	5.50	<1	0.95	<10	1.28	1448	<2	0.40	2	1596	8	0.19	15	6	130	<5	0.21	<10	<10	137	<10	116	5
130672	0.2	5.00	29	275	<0.5	<5	5.96	<1	18	12	27	4.60	<1	0.87	<10	1.05	1280	<2	0.32	2	1518	8	0.32	12	5	135	<5	0.15	<10	<10	75	<10	102	3
130673	0.2	4.34	36	297	<0.5	<5	6.00	<1	20	6	31	5.48	<1	0.85	<10	1.18	1571	<2	0.20	2	1530	4	0.29	13	5	123	<5	0.12	<10	<10	67	<10	102	3
130674	0.3	3.10	22	159	<0.5	<5	5.32	<1	18	7	28	5.02	<1	0.46	<10	1.02	1466	<2	0.13	2	1523	9	0.34	12	3	104	<5	0.08	<10	<10	42	<10	93	2
130675	<0.2	0.29	9	17	<0.5	11	>15.00	<1	2	13	2	0.37	<1	0.05	<10	5.08	162	<2	0.01	5	189	<2	0.08	<5	1	2979	<5	<0.01	<10	17	8	<10	5	<1
130676	0.5	2.32	25	116	<0.5	5	6.63	<1	19	4	29	5.39	<1	0.30	<10	0.95	1725	<2	0.02	2	1664	9	0.47	10	2	110	<5	0.02	<10	<10	30	<10	81	2
130677	0.5	2.29	34	108	<0.5	5	7.84	<1	16	4	38	5.33	<1	0.27	<10	1.03	1965	<2	0.01	2	1662	10	0.26	9	2	163	<5	0.01	<10	<10	33	<10	86	2
130678	0.5	2.51	65	102	<0.5	5	6.46	1	25	4	29	5.82	<1	0.26	<10	1.06	2026	<2	0.01	3	1652	13	0.26	9	2	123	<5	<0.01	<10	<10	37	<10	94	2
130679	0.5	2.47	38	104	<0.5	5	6.99	<1	17	4	37	5.57	<1	0.28	<10	0.99	2001	<2	0.01	2	1603	8	0.11	9	2	136	<5	<0.01	<10	<10	33	<10	94	2
130680	0.5	2.59	21	109	<0.5	5	6.99	<1	19	3	26	5.81	<1	0.28	<10	1.07	1957	<2	0.02	2	1617	10	0.16	10	2	148	<5	<0.01	<10	<10	35	<10	95	2
130681	0.3	2.45	21	97	<0.5	5	5.29	<1	16	3	23	5.40	<1	0.27	<10	1.05	1673	<2	0.01	2	1655	5	0.10	9	2	107	<5	<0.01	<10	<10	35	<10	90	2
130682	0.5	2.70	25	95	<0.5	6	7.33	<1	20	3	28	6.04	<1	0.25	<10	1.22	2184	<2	0.01	2	1711	9	0.17	10	3	177	<5	<0.01	<10	<10	39	<10	99	2
130683	0.6	2.57	31	90	<0.5	5	6.45	<1	19	3	25	5.83	<1	0.24	<10	1.22	2138	<2	0.01	2	1691	9	0.36	10	2	122	<5	<0.01	<10	<10	33	<10	94	2
130684	0.4	2.69	32	91	<0.5	6	6.76	<1	19	3	13	5.93	<1	0.23	<10	1.34	2381	<2	0.01	2	1658	8	0.11	10	2	143	<5	<0.01	<10	<10	36	<10	103	2
130685	0.9	2.48	27	97	<0.5	6	9.09	1	15	4	28	5.56	<1	0.27	<10	1.20	2611	<2	0.01	1	1565	24	0.23	9	2	196	<5	<0.01	<10	<10	31	<10	116	2
130686	1.5	2.35	75	103	0.5	5	6.61	1	16	4	28	5.17	<1	0.29	<10	0.99	2505	<2	0.01	2	1717	13	0.25	9	2	149	<5	<0.01	<10	<10	27	<10	87	2
130687	4.4	0.89	671	75	<0.5	<5	7.97	35	12	26	127	3.49	<1	0.22	<10	0.34	2484	<2	<0.01	2	808	888	1.97	<5	1	168	<5	<0.01	<10	11	12	32	2143	1
130688	2.3	1.23	181	101	<0.5	<5	3.21	44	16	15	99	4.89	<1	0.25	<10	0.48	1359	<2	0.01	3	1312	345	2.74	<5	1	63	<5	<0.01	<10	<10	18	66	4228	2
130689	4.1	0.98	262	71	<0.5	<5	6.59	20	16	19	174	4.24	<1	0.18	<10	0.39	2056	<2	0.01	3	1074	801	2.49	<5	1	115	<5	<0.01	<10	10	15	22	1425	2
130690	0.8	2.01	62	80	<0.5	5	4.88	2	15	6	41	5.47	<1	0.19	<10	0.85	2111	<2	0.01	2	1409	17	0.90	<5	2	94	<5	<0.01	<10	12	35	<10	136	2
130691	0.9	1.93	80	91	<0.5	<5	5.51	2	17	6	35	5.53	<1	0.22	<10	0.79	2243	<2	0.01	3	1454	21	1.21	<5	2	111	<5	<0.01	<10	13	31	<10	129	2
130692	1.0	2.00	39	86	<0.5	<5	5.76	3	16	5	54	4.98	<1	0.22	<10	0.84	2378	<2	0.01	3	1461	12	0.39	<5	2	104	<5	<0.01	<10	10	35	<10	323	2
130693	0.9	2.02	20	98	<0.5	5	4.80	1	21	3	30	5.54	<1	0.22	<10	0.85	2093	<2	0.01	4	1479	10	0.94	<5	2	101	<5	<0.01	<10	12	32	<10	133	2
130694	1.2	1.77	31	122	<0.5	<5	4.93	6	19	5	63	4.69	<1	0.26	<10	0.70	2094	<2	0.01	4	1487	127	0.68	<5	2	92	<5	0.01	<10	10	28	12	724	2
130695	0.3	2.06	13	106	<0.5	<5	5.05	<1	18	4	30	5.04	<1	0.24	<10	0.89	2265	<2	0.02	3	1474	6	0.35	<5	2	89	<5	0.03	<10	11	32	<10	88	2
130696	1.5	1.99	133	100	<0.5	<5	5.45	6	16	3	77	5.04	<1	0.25	<10	0.80	2247	<2	0.01	3	1456	62	0.40	<5	2	94	<5	<0.01	<10	11	28	<10	395	2
130697	0.8	2.00	81	96	<0.5	5	7.04	2	15	5	44	5.07	<1	0.24	<10	0.77	2513	<2	0.01	3	1345	14	0.66	<5	2	150	<5	0.01	<10	13	31	<10	148	2
130698	0.4	2.16	15	96	<0.5	<5	5.80	<1	18	2	33	5.30	<1	0.23	<10	0.91	2188	<2	0.02	3	1431	7	0.48	<5	2	104	<5	0.01	<10	11	38	<10	94	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth /shipment33-b

Sample type: core

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3634RJ

Date : Oct-24-08

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
130699	0.5	2.50	16	94	<0.5	5	5.58	<1	24	2	37	6.21	<1	0.22	<10	1.10	2212	<2	0.01	5	1488	6	0.26	<5	3	110	<5	<0.01	<10	13	41	<10	107	3
130700	>200.0	0.55	570	179	<0.5	101	0.54	22	7	19	7516	2.19	6	0.14	<10	0.54	275	545	0.02	5	391	865	1.11	1658	1	69	<5	0.05	<10	<10	18	<10	949	2
130701	1.2	1.89	17	89	<0.5	<5	6.11	<1	17	4	43	4.62	<1	0.22	<10	0.83	1886	<2	0.02	3	1409	9	0.25	<5	2	98	<5	0.01	<10	<10	30	<10	84	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Quality Assaying for over 25 Years

Assay Certificate

8V-3671-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 34-a**
Attn: **Sue Deane**

Oct-28-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
121968	<0.01	0.01	0.8
121969	<0.01		0.2
121970	<0.01		0.4
121971	<0.01		<0.1
121972	<0.01		0.1
121973	0.35		<0.1
121974	<0.01		<0.1
121975	<0.01		<0.1
121976	<0.01		<0.1
121977	<0.01	0.01	<0.1
121978	0.03		<0.1
121979	0.01		<0.1
121980	0.01		<0.1
121981	0.10		<0.1
121982	0.07		0.1
121983	0.07		<0.1
121984	0.01		0.1
121985	<0.01		<0.1
121986	0.01		<0.1
121987	<0.01	<0.01	<0.1
121988	<0.01		<0.1
121989	<0.01		<0.1
*0211	2.14		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3671-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 34-a**
Attn: **Sue Deane**

Oct-28-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Zn %
121990	<0.01	<0.01	1.9	
121991	<0.01		<0.1	
121992	<0.01		0.9	
121993	<0.01		0.3	
121994	<0.01		<0.1	
121995	<0.01		<0.1	
121996	0.28		1.5	
121997	0.12		1.2	
121998	0.30		1.2	
121999	0.41	0.43	1.2	
122000	<0.01		<0.1	
122001	0.11		1.2	
122002	0.23		1.5	
122003	0.05		1.2	
122004	0.13		1.8	
122005	0.12		1.6	
122006	0.45		1.7	
122007	0.55		2.1	
122008	0.66		2.4	
122009	0.16	0.16	2.4	
122010	0.15		19.5	1.38
122011	0.05		1.7	
*0211	2.18			
*CCu-1c				3.96
*BLANK	<0.01			<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3671-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 34-a**
Attn: **Sue Deane**

Oct-28-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
122012	0.19	0.21	1.8	
122013	0.32		2.1	
122014	0.17		2.7	
122015	0.09		3.2	
122016	0.12		2.6	
122017	0.15		2.7	
122018	0.17		2.0	
122019	0.41		3.2	
122020	2.66		5.4	
122021	0.03	0.03	0.9	
122022	0.05		0.2	
122023	0.01		0.8	
122024	0.02		0.6	
122025	0.14		>200	784.8
122026	0.01		1.1	
122027	0.01		<0.1	
122028	0.01		0.2	
122029	0.01		0.4	
122030	<0.01		<0.1	
122031	0.01	0.01	0.9	
122032	0.01		2.0	
122033	0.02		0.6	
*0211	2.19			
*CCu-1c				129.4
*BLANK	<0.01			<0.1

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3671-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 34-a**
Attn: **Sue Deane**

Oct-28-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122034	0.06	0.06	2.0
122035	0.02		0.3
122036	0.03		1.0
122037	0.01		0.4
122038	0.01		<0.1
122039	0.02		<0.1
122040	0.02		<0.1
122041	0.01		<0.1
122042	0.02		<0.1
122043	0.02	0.02	0.4
122044	0.01		0.5
122045	0.07		1.6
122046	0.01		<0.1
122047	0.06		3.9
122048	4.95		34.4
122049	0.02		1.0
122050	<0.01		<0.1
122051	0.08		1.2
122052	0.05		0.2
122053	<0.01	<0.01	<0.1
122054	0.01		<0.1
122055	<0.01		0.1
*0211	2.14		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3671-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 34-a**
Attn: **Sue Deane**

Oct-28-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
122056	0.01	0.01	<0.1	
122057	0.01		<0.1	
122058	0.07		0.3	
122059	9.48		2.3	
122060	0.04		0.6	
122061	0.83		0.7	
122062	0.12		0.8	
122063	0.15		1.1	
122064	0.06		0.8	
122065	0.01	0.02	0.3	
122066	0.01		0.5	
122067	0.01		0.1	
122068	<0.01		0.1	
122069	<0.01		<0.1	
122070	0.01		0.2	
122071	0.01		0.3	
122072	0.02		0.2	
122073	<0.01		<0.1	
122074	0.01		0.1	
122075	0.12	0.14	>200	792.1
122076	<0.01		0.8	
122077	0.01		0.4	
*0211	2.15			
*CCu-1c				128.3
*BLANK	<0.01			<0.1

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3671-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 34-a**
Attn: **Sue Deane**

Oct-28-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122078	<0.01	0.01	0.3
122079	<0.01		<0.1
122080	<0.01		<0.1
122081	0.06		1.2
122082	<0.01		<0.1
122083	0.02		0.2
122084	<0.01		0.2
122085	0.09		0.3
122086	0.08		0.5
122087	0.07	0.09	0.9
122088	0.01		0.3
122089	0.01		0.6
122090	0.04		0.9
122091	0.02		0.4
122092	0.15		1.2
122093	0.02		3.4
122094	0.01		0.3
122095	0.01		<0.1
122096	<0.01		<0.1
122097	0.12	0.12	0.1
122098	<0.01		<0.1
122099	0.01		<0.1
*0211	2.21		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3671-RA7

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 34-a**
Attn: **Sue Deane**

Oct-28-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122100	<0.01	<0.01	<0.1
122101	0.01		0.5
122102	0.01		0.3
122103	0.01		0.1
122104	0.04		0.6
122105	0.01		0.2
122106	0.02		0.1
122107	0.01		0.2
122108	0.02		1.5
122109	0.01	0.02	0.4
122110	0.01		0.3
122111	0.02		0.3
122112	0.01		0.5
122113	0.01		0.3
122114	0.01		0.2
122115	0.01		0.5
122116	0.01		0.5
122117	0.02		0.2
122118	0.12		0.4
122119	0.03	0.02	0.8
122120	0.01		0.3
122121	<0.01		0.3
*0211	2.19		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3671-RA8

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 34-a**
Attn: **Sue Deane**

Oct-28-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Ag g/tonne
122122	0.01	0.01	0.1	
122123	0.01		0.1	
122124	0.05		<0.1	
122125	0.13		>200	787.5
122126	0.03		0.8	
122127	0.06		0.7	
122128	0.46		0.6	
122129	0.17		<0.1	
122130	0.02		0.2	
122131	0.02	<0.01	0.5	
122132	0.10		1.4	
122133	0.06		1.3	
122134	0.06		0.7	
122135	0.01		<0.1	
122136	0.02		0.1	
122137	0.04		<0.1	
122181	0.01		0.2	
122182	0.02		0.3	
122183	0.01		0.4	
122184	0.02	0.01	1.1	
122185	0.64		2.4	
122186	0.03		1.8	
*0211	2.25			
*CCu-1c				127.9
*BLANK	<0.01			<0.1

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3671-RA9

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 34-a**
Attn: **Sue Deane**

Oct-28-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne	Pb %	Zn %
122187	0.10	0.07	1.8		
122188	0.32		6.3		
122189	0.09		2.0		
122190	0.08		1.6		
122191	0.35		5.1		
122192	0.42		3.2		
122193	0.14		2.2		
122194	0.12		2.9		
122195	0.19		4.2		
122196	0.10	0.09	2.4		
122197	0.16		3.5		
122198	2.08		56.1	2.06	5.03
122199	0.77		18.5		1.01
122200	<0.01		<0.1		
122201	0.92		22.1		1.05
122202	0.18		1.4		
122203	0.18		4.5		
122204	0.21		4.0		
122205	0.05		1.1		
122206	0.07	0.06	0.7		
122207	0.52		4.2		
122208	0.44		16.6		
*0211	2.19				
*CCu-1c				0.34	3.97
*BLANK	<0.01			<0.01	<0.01

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3671-RA10

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 34-a**
Attn: **Sue Deane**

Oct-28-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122209	0.12	0.13	3.5
122210	0.43		11.0
122211	0.34		15.9
122212	<0.01		1.3
122213	0.02		1.5
122214	0.08		1.7
122215	0.13		2.7
122216	0.07		2.7
122217	0.11		2.4
122218	0.14	0.16	5.6
122219	0.20		3.5
122220	0.16		2.9
122221	0.11		1.5
122222	0.13		2.1
122223	0.04		1.7
122224	0.11		1.6
122225	1.52		0.3
122226	0.09		1.3
122227	0.15		1.9
122228	0.07	0.08	1.5
122229	0.35		1.9
122230	0.22		4.6
*0211	2.12		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3671-RA11

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 34-a**
Attn: **Sue Deane**

Oct-28-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122231	1.49	1.52	80.0
122232	4.58		169
122233	0.25		21.4
122234	0.09		2.9
122235	0.05		1.6
122236	0.05		1.0
122237	0.04		0.7
122238	0.02		0.5
122239	0.04		0.8
122240	0.01	0.01	0.8
122241	0.04		7.1
122242	0.04		1.6
122243	0.03		3.4
122244	0.05		2.9
122245	0.06		2.2
122246	0.03		1.3
122247	0.02		1.0
122248	0.03		0.8
122249	0.02		1.9
122250	<0.01	<0.01	<0.1
122251	0.02		1.0
122252	0.09		0.9
*0211	2.20		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3671-RA12

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 34-a**
Attn: **Sue Deane**

Oct-28-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122253	0.14	0.12	1.6
122254	0.04		8.5
122255	0.06		5.5
122256	0.05		3.7
122257	0.06		3.5
122258	0.05		3.4
122259	0.03		3.0
122260	0.02		3.0
122261	0.09		2.1
122262	0.10	0.10	3.8
122263	0.05		5.2
122264	0.02		2.2
122265	0.04		1.7
122266	0.03		1.6
122267	0.01		2.2
122268	0.04		2.0
122269	0.21		2.1
122270	0.13		3.1
122271	0.42		1.7
122272	0.14	0.15	0.9
122273	0.11		1.9
122274	0.47		2.0
*0211	2.09		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3671-RA13

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment 34-a**
Attn: **Sue Deane**

Oct-28-08

We hereby certify the following assay of 14 core samples
submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122275	<0.01	<0.01	<0.1
122276	0.03		1.3
122277	0.05		5.5
122278	0.12		4.0
122279	0.05		3.0
122280	0.17		4.6
122281	0.01		1.1
122282	0.02		1.1
122283	0.03		1.0
122284	0.05	0.04	1.8
122285	0.06		3.9
122286	0.03		2.9
122287	0.04		2.4
122288	0.03		2.8
*0211	2.22		
*BLANK	<0.01		

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3671RJ

Date : Oct-28-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 34-a

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121968	0.8	1.81	16	131	<0.5	<5	4.37	6	14	15	27	4.43	<1	0.40	<10	0.95	1705	3	0.03	3	1567	391	0.62	<5	3	147	<5	0.06	<10	<10	50	<10	405	2
121969	0.2	1.85	19	107	<0.5	<5	4.36	5	16	17	37	4.66	<1	0.28	<10	1.10	1886	2	0.02	4	1604	96	0.70	<5	3	172	<5	0.03	<10	<10	48	<10	333	2
121970	0.4	2.28	15	145	<0.5	<5	4.05	2	20	14	39	5.33	<1	0.43	<10	1.32	1927	<2	0.03	4	1658	304	0.81	<5	3	132	<5	0.06	<10	12	60	<10	145	3
121971	<0.2	1.70	7	107	<0.5	<5	4.07	1	16	14	23	4.14	<1	0.29	<10	0.92	1733	<2	0.02	3	1503	39	0.33	<5	3	123	<5	0.06	<10	<10	45	<10	99	2
121972	<0.2	1.71	5	126	<0.5	<5	3.37	1	14	10	33	4.06	<1	0.33	<10	0.86	1514	<2	0.03	3	1467	56	0.45	<5	4	114	<5	0.04	<10	<10	45	<10	85	2
121973	<0.2	1.84	<5	112	<0.5	5	6.17	1	15	11	23	4.35	<1	0.29	<10	1.28	1933	<2	0.02	2	1456	25	0.33	<5	3	251	<5	0.04	<10	10	49	<10	83	4
121974	<0.2	1.82	<5	122	<0.5	<5	3.93	1	14	9	34	4.25	<1	0.33	10	0.99	1641	<2	0.03	3	1519	47	0.23	<5	3	135	<5	0.04	<10	<10	47	<10	97	2
121975	<0.2	0.18	<5	<10	<0.5	8	>15.00	<1	2	22	3	0.27	<1	0.02	<10	5.77	183	<2	0.01	5	198	<2	0.07	<5	1	2166	<5	<0.01	<10	<10	5	<10	15	<1
121976	<0.2	1.91	<5	131	<0.5	<5	4.29	1	16	12	19	4.42	<1	0.39	<10	0.95	1816	<2	0.03	3	1504	41	0.35	<5	3	139	<5	0.09	<10	<10	46	<10	97	2
121977	<0.2	1.67	<5	113	<0.5	<5	3.66	1	13	13	23	3.86	<1	0.32	<10	0.80	1697	<2	0.02	3	1449	36	0.13	<5	3	137	<5	0.07	<10	<10	36	<10	89	2
121978	<0.2	1.44	24	110	<0.5	<5	5.18	1	13	19	27	3.55	<1	0.36	<10	0.68	1782	<2	0.02	2	1337	23	0.64	<5	2	163	<5	0.04	<10	<10	30	<10	64	2
121979	<0.2	1.65	20	90	<0.5	<5	6.26	1	15	11	27	4.12	<1	0.29	<10	0.89	2293	<2	0.02	2	1426	33	0.53	<5	2	169	<5	0.07	<10	<10	40	<10	83	2
121980	<0.2	1.65	9	145	<0.5	<5	6.37	1	13	12	31	3.73	<1	0.37	<10	0.83	2061	<2	0.03	1	1320	18	0.29	<5	3	191	<5	0.07	<10	<10	40	<10	71	2
121981	<0.2	1.53	14	94	<0.5	5	6.82	1	12	10	44	3.70	<1	0.29	<10	0.83	2251	<2	0.02	2	1346	26	0.51	<5	2	170	<5	0.02	<10	<10	36	<10	74	2
121982	<0.2	1.74	16	127	<0.5	<5	6.31	1	18	9	36	3.83	<1	0.40	<10	0.93	2272	<2	0.02	3	1400	19	0.31	<5	3	191	<5	0.04	<10	<10	45	<10	73	2
121983	<0.2	1.97	14	106	<0.5	<5	3.26	1	21	7	49	4.53	<1	0.33	<10	1.14	1870	<2	0.02	3	1585	22	0.23	<5	2	119	<5	0.06	<10	10	46	<10	93	2
121984	<0.2	2.32	53	120	<0.5	<5	4.01	2	20	8	37	5.33	<1	0.33	<10	1.38	2520	<2	0.02	3	1483	25	0.44	<5	3	124	<5	0.06	<10	14	57	<10	99	2
121985	<0.2	1.76	9	287	<0.5	<5	4.56	1	15	16	33	3.91	<1	0.31	10	1.04	1841	<2	0.02	3	1631	21	0.26	<5	3	140	<5	0.12	<10	<10	48	<10	81	4
121986	<0.2	1.86	14	124	<0.5	<5	3.23	1	18	11	47	4.22	<1	0.37	<10	1.04	1700	<2	0.02	3	1594	21	0.46	<5	3	122	<5	0.08	<10	<10	54	<10	90	2
121987	<0.2	1.54	14	100	<0.5	<5	2.89	1	16	11	39	3.47	<1	0.30	<10	0.89	1468	<2	0.02	4	1588	26	0.31	<5	3	108	<5	0.08	<10	<10	50	<10	77	2
121988	<0.2	1.46	23	102	<0.5	<5	6.23	1	12	19	11	3.28	<1	0.38	<10	0.80	1995	<2	0.02	2	1251	26	0.60	<5	2	235	<5	0.02	<10	<10	27	<10	64	2
121989	<0.2	1.23	13	97	<0.5	<5	4.07	1	10	15	10	2.67	<1	0.33	<10	0.63	1474	<2	0.02	2	1399	25	0.44	<5	2	142	<5	0.03	<10	<10	21	<10	53	1
121990	1.9	2.05	38	131	<0.5	<5	4.89	3	15	12	92	4.20	<1	0.42	<10	1.08	2014	<2	0.02	2	1537	1163	0.37	<5	3	165	<5	0.04	<10	<10	40	<10	175	2
121991	<0.2	1.49	23	110	<0.5	<5	5.70	1	13	18	14	3.35	<1	0.36	<10	0.83	1876	<2	0.02	2	1588	37	0.58	<5	2	191	<5	0.02	<10	<10	31	<10	79	2
121992	0.9	1.77	24	113	<0.5	6	4.73	5	15	12	62	4.07	<1	0.33	10	0.98	1911	<2	0.02	2	1574	781	0.43	<5	2	164	<5	0.01	<10	<10	33	11	486	2
121993	0.3	2.09	84	96	<0.5	5	4.95	3	17	10	45	4.95	<1	0.29	11	1.15	2261	<2	0.02	2	1603	200	0.43	<5	2	153	<5	0.03	<10	<10	38	<10	94	2
121994	<0.2	2.10	12	112	<0.5	<5	4.62	1	16	7	39	4.54	<1	0.34	<10	1.23	2075	<2	0.03	2	1568	32	0.33	<5	3	144	<5	0.07	<10	<10	44	<10	86	2
121995	<0.2	2.00	21	93	<0.5	<5	6.99	1	15	10	35	4.40	<1	0.29	<10	1.16	2560	<2	0.02	2	1449	39	0.35	<5	3	166	<5	0.06	<10	<10	37	<10	77	2
121996	1.5	1.84	7	97	<0.5	5	4.83	4	17	10	287	4.30	<1	0.24	<10	1.23	1826	51	0.03	3	1380	22	0.40	<5	4	235	<5	0.02	<10	<10	56	14	445	3
121997	1.2	0.99	20	90	<0.5	6	5.03	6	20	10	210	5.32	<1	0.27	<10	1.16	2340	43	0.01	4	1511	54	0.71	<5	5	278	<5	<0.01	<10	<10	33	10	550	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3671RJ

Date : Oct-28-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 34-a

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
121998	1.2	2.00	10	101	<0.5	<5	4.42	2	17	11	167	4.77	<1	0.30	<10	1.28	2056	70	0.02	3	1517	22	0.41	<5	5	165	<5	0.05	<10	<10	63	<10	210	3
121999	1.2	1.71	17	75	<0.5	<5	5.89	2	11	36	140	4.21	<1	0.13	<10	1.03	2131	47	0.01	2	827	22	0.31	<5	3	202	<5	0.03	<10	<10	52	<10	194	2
122000	<0.2	0.07	<5	<10	<0.5	10	>15.00	<1	1	9	4	0.10	<1	0.02	<10	3.17	97	<2	0.01	<1	100	<2	0.02	<5	<1	3834	<5	<0.01	<10	<10	2	<10	6	<1
122001	1.2	1.36	20	233	<0.5	5	4.45	3	13	16	215	4.52	<1	0.23	<10	0.99	2100	30	0.01	2	1403	21	0.53	<5	3	218	<5	<0.01	<10	<10	46	<10	209	2
122002	1.5	1.79	46	140	<0.5	5	3.69	3	14	11	240	4.56	<1	0.32	<10	0.90	1796	62	0.02	2	1375	32	0.74	<5	3	138	<5	0.01	<10	<10	55	<10	281	2
122003	1.2	1.81	57	103	<0.5	6	4.21	3	13	11	153	4.34	<1	0.37	10	0.91	2055	52	0.01	2	1640	22	0.86	<5	3	89	<5	<0.01	<10	<10	50	<10	215	2
122004	1.8	2.10	29	84	<0.5	5	3.94	3	16	12	242	4.94	<1	0.35	<10	1.13	2120	77	0.01	3	1410	34	0.75	<5	3	88	<5	0.02	<10	<10	58	<10	255	2
122005	1.6	1.97	32	77	<0.5	6	3.93	2	16	15	234	4.93	<1	0.25	<10	1.03	2194	78	0.01	3	1394	29	0.64	<5	3	89	<5	0.01	<10	<10	60	<10	166	2
122006	1.7	2.04	42	89	<0.5	<5	3.20	5	19	17	251	5.47	<1	0.30	<10	0.95	2059	110	0.01	5	1442	28	1.02	<5	4	74	<5	0.04	<10	<10	73	<10	397	3
122007	2.1	1.77	59	89	<0.5	<5	3.44	7	22	14	239	4.42	<1	0.30	10	0.89	1829	54	0.01	4	1391	229	0.96	<5	3	77	<5	0.03	<10	<10	50	10	539	2
122008	2.4	1.84	55	105	<0.5	5	3.77	10	17	19	412	4.90	<1	0.30	<10	0.82	2158	29	0.01	4	1392	43	0.75	<5	4	94	<5	0.01	<10	<10	65	11	673	2
122009	2.4	1.61	138	87	<0.5	6	5.53	7	15	16	260	4.76	<1	0.23	<10	0.77	2704	45	0.01	3	1477	36	1.10	<5	4	103	<5	<0.01	<10	11	73	<10	374	2
122010	19.5	1.00	186	53	<0.5	9	>15.00	146	19	15	1114	5.43	<1	0.15	<10	0.55	4609	23	0.01	2	654	3090	4.49	<5	4	302	<5	<0.01	<10	12	41	238	>10000	1
122011	1.7	1.14	60	107	<0.5	8	11.21	5	14	16	139	4.39	<1	0.21	<10	0.69	3900	50	0.01	2	1165	34	0.58	<5	4	207	<5	<0.01	<10	<10	45	<10	396	1
122012	1.8	2.23	34	116	<0.5	5	6.97	3	16	10	227	5.19	<1	0.38	<10	1.32	2627	39	0.01	3	1421	28	0.58	<5	4	200	<5	0.01	<10	<10	56	<10	258	2
122013	2.1	1.82	69	77	<0.5	5	5.93	4	16	10	237	4.31	<1	0.28	<10	1.04	2109	76	0.01	2	1375	28	0.60	<5	3	182	<5	0.02	<10	<10	48	<10	252	2
122014	2.7	2.01	44	85	<0.5	<5	4.82	4	13	11	267	4.75	<1	0.24	<10	1.23	2081	60	0.02	2	1272	30	0.67	<5	4	120	<5	0.01	<10	<10	65	<10	311	2
122015	3.2	2.20	70	107	<0.5	5	2.97	5	16	14	314	6.09	<1	0.24	<10	1.35	2130	48	0.01	3	1392	30	1.26	<5	3	91	<5	<0.01	<10	<10	58	<10	298	2
122016	2.6	2.06	59	90	<0.5	<5	4.24	4	14	14	245	4.88	<1	0.30	<10	1.19	2367	76	0.01	3	1288	28	0.89	<5	3	93	<5	0.04	<10	<10	57	10	314	2
122017	2.7	1.10	93	54	<0.5	<5	11.71	6	11	13	191	3.55	<1	0.17	<10	0.68	3058	29	0.01	3	969	67	1.39	<5	3	197	<5	0.01	<10	<10	33	<10	428	1
122018	2.0	2.10	69	99	<0.5	<5	4.90	5	17	13	223	4.72	<1	0.31	<10	1.10	2439	58	0.01	3	1253	40	0.80	<5	3	85	<5	0.11	<10	<10	57	<10	275	2
122019	3.2	1.39	219	45	<0.5	5	10.06	9	17	95	186	4.44	<1	0.12	<10	0.92	2987	29	0.01	16	1049	73	1.97	<5	7	138	<5	0.05	<10	12	72	<10	309	2
122020	5.4	2.42	212	59	<0.5	5	10.18	9	32	210	193	6.58	<1	0.12	<10	1.81	3074	8	0.01	35	1599	123	2.36	<5	19	181	<5	0.09	<10	<10	169	<10	317	3
122021	0.9	2.26	79	57	<0.5	8	10.55	4	23	173	83	4.99	<1	0.09	<10	1.91	2948	6	0.01	23	1486	51	0.51	<5	17	217	<5	0.01	<10	<10	159	<10	128	2
122022	0.2	2.24	59	46	<0.5	<5	14.79	3	27	224	76	4.73	<1	0.05	<10	2.03	3589	<2	0.01	29	1573	35	0.59	<5	17	215	<5	0.08	<10	11	172	<10	80	3
122023	0.8	2.56	49	44	<0.5	<5	6.56	4	33	243	111	5.52	<1	0.05	<10	2.33	1802	<2	0.01	34	1987	46	0.60	<5	11	129	<5	0.16	<10	<10	183	<10	100	4
122024	0.6	2.73	48	50	<0.5	<5	10.58	4	31	260	99	5.35	1	0.06	<10	2.40	3341	3	0.01	36	1860	47	0.35	<5	19	263	<5	0.12	<10	13	189	<10	219	5
122025	>200.0	0.67	575	177	<0.5	108	0.55	22	6	22	7593	2.19	6	0.15	<10	0.57	272	551	0.03	5	462	865	1.11	1714	2	77	<5	0.06	<10	<10	18	<10	816	2
122026	1.1	1.65	40	52	<0.5	8	11.41	12	25	166	73	4.83	<1	0.12	<10	1.77	3290	9	0.01	30	1543	1336	0.76	<5	15	332	<5	0.01	<10	14	108	20	1055	2
122027	<0.2	2.60	17	215	<0.5	<5	10.49	2	24	233	8	4.67	<1	0.06	<10	2.63	2794	4	0.01	31	1654	39	0.16	<5	15	290	<5	0.09	<10	<10	146	<10	111	7

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3671RJ

Date : Oct-28-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 34-a

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122028	0.2	2.65	34	166	<0.5	<5	8.98	6	30	259	104	4.66	<1	0.04	<10	2.77	2397	<2	0.01	34	1916	61	0.23	<5	13	208	<5	0.11	<10	<10	170	<10	446	6
122029	0.4	2.46	35	83	<0.5	<5	5.28	3	20	134	30	5.11	<1	0.15	<10	2.02	1954	<2	0.02	17	1617	58	0.37	<5	12	140	<5	0.09	<10	<10	133	<10	124	4
122030	<0.2	2.69	43	209	<0.5	5	11.73	3	28	208	19	5.97	<1	0.13	<10	2.28	2639	<2	0.01	33	1764	23	0.33	<5	16	339	<5	0.06	<10	<10	157	<10	104	6
122031	0.9	2.06	47	48	<0.5	<5	9.52	10	29	232	115	4.43	<1	0.05	<10	1.89	2430	2	0.01	31	1823	256	0.41	<5	12	220	<5	0.14	<10	<10	158	13	725	8
122032	2.0	2.13	42	48	<0.5	<5	6.47	22	29	188	148	4.69	<1	0.05	<10	2.04	2102	<2	0.01	32	1929	1303	0.79	<5	8	134	<5	0.13	<10	<10	143	34	2011	5
122033	0.6	2.02	35	73	<0.5	<5	5.59	13	26	208	46	3.84	1	0.09	<10	2.23	1541	3	0.03	33	2031	366	0.31	<5	8	113	<5	0.18	<10	<10	155	22	1245	5
122034	2.0	2.42	212	34	<0.5	8	14.46	12	27	218	121	6.52	3	0.04	<10	2.02	4281	2	0.01	30	1403	201	1.60	<5	18	267	<5	0.04	<10	18	171	12	665	5
122035	0.3	2.36	90	57	<0.5	<5	10.66	4	32	258	68	5.50	2	0.06	<10	2.02	2495	<2	0.02	37	1911	22	0.46	<5	16	182	<5	0.13	<10	<10	194	<10	92	9
122036	1.0	2.41	117	34	<0.5	<5	13.23	5	33	229	113	5.63	1	0.03	<10	2.28	2989	10	0.01	36	1704	27	0.91	<5	15	237	<5	0.08	<10	<10	184	<10	94	5
122037	0.4	2.30	65	39	<0.5	<5	12.81	3	35	239	138	4.83	1	0.04	<10	2.29	2533	3	0.02	36	1872	22	0.49	<5	12	221	<5	0.11	<10	<10	167	<10	79	8
122038	<0.2	1.95	38	36	<0.5	<5	9.45	2	26	215	6	4.12	1	0.04	<10	1.85	1540	<2	0.02	32	1963	12	0.05	<5	9	182	<5	0.12	<10	<10	144	<10	51	8
122039	<0.2	2.50	42	27	<0.5	<5	>15.00	3	27	198	10	5.19	1	0.04	<10	1.96	2661	<2	0.01	29	1513	12	0.10	<5	17	254	<5	0.10	<10	<10	148	<10	92	8
122040	<0.2	2.03	61	24	<0.5	<5	>15.00	5	26	189	18	4.73	<1	0.02	<10	1.67	2521	<2	0.01	26	1260	18	0.24	<5	19	415	<5	0.08	<10	<10	140	170	104	5
122041	<0.2	2.74	43	107	<0.5	<5	13.26	3	28	241	7	5.68	1	0.09	<10	2.21	2773	<2	0.01	34	1851	17	0.13	<5	22	261	<5	0.10	<10	<10	180	<10	91	9
122042	<0.2	2.36	58	46	<0.5	6	>15.00	3	22	177	7	5.36	<1	0.07	<10	1.93	4545	<2	0.01	28	1347	13	0.35	<5	17	355	<5	0.06	<10	16	126	<10	65	4
122043	0.4	2.54	106	45	<0.5	<5	>15.00	6	27	222	60	5.79	<1	0.05	<10	2.21	4251	<2	0.01	31	1462	171	0.49	<5	21	323	<5	0.07	<10	15	176	<10	258	3
122044	0.5	2.84	61	39	<0.5	<5	9.35	5	32	285	87	6.40	1	0.05	<10	2.67	2790	<2	0.01	38	1931	43	0.77	<5	24	205	<5	0.11	<10	14	227	<10	219	3
122045	1.6	1.73	209	42	<0.5	6	>15.00	10	29	152	43	7.71	<1	0.05	<10	1.63	4277	<2	0.01	19	1015	76	4.46	<5	14	277	<5	0.06	<10	19	121	10	521	3
122046	<0.2	2.85	57	34	<0.5	<5	14.05	9	29	194	15	7.38	1	0.02	<10	2.45	3144	<2	0.01	29	1333	26	0.89	<5	19	278	<5	0.08	<10	18	163	13	678	6
122047	3.9	2.97	160	44	<0.5	<5	11.35	56	38	223	148	7.99	1	0.04	<10	2.67	3403	2	0.01	30	1521	688	2.18	<5	22	234	<5	0.10	<10	12	203	76	4763	5
122048	34.4	2.70	163	39	<0.5	<5	10.42	7	40	286	146	6.44	1	0.05	<10	2.48	2800	<2	0.01	35	2001	69	0.75	<5	23	234	<5	0.13	<10	13	226	<10	204	4
122049	1.0	2.45	84	46	<0.5	<5	8.94	5	38	270	131	5.42	1	0.07	<10	2.57	1991	<2	0.02	42	1993	63	0.66	<5	11	207	<5	0.16	<10	<10	196	<10	164	5
122050	<0.2	0.09	<5	<10	<0.5	9	>15.00	<1	1	16	4	0.20	<1	0.01	<10	5.20	194	<2	0.01	1	184	<2	0.02	<5	1	3241	<5	<0.01	<10	<10	6	<10	7	<1
122051	1.2	2.70	115	59	<0.5	<5	10.24	6	40	235	117	8.12	<1	0.08	<10	2.71	2953	<2	0.01	35	1629	77	3.17	<5	17	232	<5	0.11	<10	18	191	<10	142	6
122052	0.2	2.40	158	40	<0.5	5	14.52	6	33	264	67	6.10	1	0.06	<10	2.24	3156	2	0.01	38	1762	40	0.75	<5	21	315	<5	0.07	<10	12	206	<10	106	3
122053	<0.2	2.37	44	45	<0.5	<5	9.39	4	29	266	81	5.70	1	0.06	<10	2.34	2040	2	0.02	35	1568	42	0.53	<5	19	264	<5	0.05	<10	<10	195	<10	87	4
122054	<0.2	1.66	42	40	<0.5	9	>15.00	4	25	199	50	5.63	1	0.06	<10	1.89	3304	<2	0.01	32	1520	35	0.91	<5	21	364	<5	<0.01	<10	12	143	<10	159	2
122055	<0.2	2.75	20	61	<0.5	<5	6.68	3	33	301	83	6.27	1	0.10	<10	3.02	1879	<2	0.02	38	2017	40	0.75	<5	11	195	<5	0.14	<10	12	199	<10	91	4
122056	<0.2	2.73	31	53	<0.5	<5	13.19	4	33	308	77	6.18	4	0.05	<10	2.45	2883	<2	0.01	40	1989	34	0.43	<5	28	320	<5	0.13	<10	<10	233	<10	98	7
122057	<0.2	2.30	27	59	<0.5	<5	13.61	2	28	285	64	5.87	2	0.06	<10	1.79	2880	<2	0.02	36	1859	24	0.39	<5	27	294	<5	0.14	<10	11	220	<10	73	4

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3671RJ

Date : Oct-28-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 34-a

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122058	0.3	3.07	37	44	<0.5	<5	9.05	3	36	309	108	7.04	1	0.07	<10	2.61	2439	<2	0.01	42	2033	35	0.62	<5	26	264	<5	0.10	<10	15	228	<10	93	4
122059	2.3	3.55	44	56	<0.5	7	6.72	3	39	286	105	7.25	1	0.15	<10	3.06	2600	<2	0.01	46	2024	38	0.45	<5	18	164	<5	0.02	<10	12	198	<10	110	3
122060	0.6	3.01	50	50	<0.5	9	10.32	10	26	150	95	6.53	1	0.13	<10	2.43	3092	3	0.01	24	1663	125	0.72	<5	13	243	<5	0.01	<10	11	161	10	475	3
122061	0.7	2.79	41	162	<0.5	7	4.67	4	27	118	71	6.27	<1	0.27	<10	1.89	2044	<2	0.01	27	1998	40	0.64	<5	11	101	<5	0.01	<10	<10	125	<10	156	3
122062	0.8	2.71	47	123	<0.5	8	4.26	3	32	57	105	7.00	<1	0.22	<10	1.93	2026	2	0.01	17	2311	43	0.70	<5	9	106	<5	<0.01	<10	<10	104	<10	122	3
122063	1.1	2.50	58	109	<0.5	6	2.60	4	28	56	119	6.18	<1	0.28	<10	1.55	1729	<2	0.01	17	2138	76	0.50	<5	7	61	<5	<0.01	<10	<10	91	<10	237	2
122064	0.8	2.14	59	73	<0.5	8	3.75	3	28	60	104	6.48	<1	0.21	<10	1.31	1559	<2	0.01	17	1320	51	1.54	<5	8	102	<5	<0.01	<10	<10	86	<10	96	3
122065	0.3	0.75	45	141	<0.5	6	4.53	3	21	7	67	4.40	<1	0.32	<10	0.56	1845	7	0.01	4	1965	104	0.52	<5	4	120	<5	<0.01	<10	<10	21	<10	171	2
122066	0.5	1.32	33	100	<0.5	7	4.67	2	23	8	130	5.38	<1	0.31	<10	1.28	2003	<2	0.02	5	1874	15	0.59	<5	5	212	<5	<0.01	<10	<10	40	<10	61	2
122067	<0.2	1.71	20	135	<0.5	6	4.32	1	19	8	61	5.13	<1	0.37	10	1.40	1926	<2	0.02	4	1854	16	0.24	<5	5	199	<5	<0.01	<10	<10	51	<10	72	2
122068	<0.2	2.18	17	122	<0.5	6	5.31	2	24	7	72	5.61	<1	0.31	<10	1.38	2036	2	0.02	6	1813	31	0.28	<5	4	163	<5	0.01	<10	<10	54	<10	104	3
122069	<0.2	2.77	9	112	<0.5	8	3.95	1	27	7	62	6.73	<1	0.39	<10	1.33	1852	<2	0.03	6	1747	21	0.30	<5	5	139	<5	0.01	<10	<10	91	<10	104	3
122070	0.2	2.76	14	112	<0.5	7	3.53	1	25	7	62	6.58	1	0.29	<10	1.55	1985	<2	0.01	6	1786	114	0.43	<5	4	118	<5	<0.01	<10	10	69	<10	109	3
122071	0.3	2.67	18	105	<0.5	6	3.10	3	22	8	46	6.36	1	0.38	<10	1.37	2020	<2	0.02	4	1692	66	0.61	<5	4	96	<5	0.02	<10	<10	69	<10	284	3
122072	0.2	2.40	22	49	<0.5	<5	6.20	6	18	9	46	4.80	<1	0.17	<10	2.06	2147	<2	0.02	3	1604	327	0.38	<5	4	180	<5	0.07	<10	<10	66	20	502	2
122073	<0.2	2.69	7	110	<0.5	<5	4.46	2	20	7	59	6.00	<1	0.35	<10	1.52	1944	<2	0.03	4	1676	35	0.30	<5	5	123	<5	0.12	<10	<10	82	<10	111	3
122074	<0.2	2.75	11	128	<0.5	<5	4.82	2	22	6	77	6.56	<1	0.27	<10	1.53	2444	<2	0.01	4	1659	35	0.55	<5	4	139	<5	0.09	<10	<10	73	<10	103	3
122075	>200.0	0.60	599	175	<0.5	113	0.56	23	7	21	7608	2.21	7	0.15	<10	0.58	279	573	0.03	5	480	912	1.15	1800	1	75	<5	0.05	<10	<10	17	<10	937	2
122076	0.8	2.67	5	111	<0.5	<5	5.60	1	21	6	76	5.64	<1	0.35	<10	1.60	2245	<2	0.03	4	1633	24	0.23	<5	5	129	<5	0.12	<10	<10	85	<10	97	3
122077	0.4	2.00	30	94	<0.5	<5	4.45	2	24	8	57	4.62	<1	0.33	<10	1.07	2042	<2	0.01	5	1699	50	0.54	<5	3	111	<5	0.11	<10	<10	57	<10	77	2
122078	0.3	3.03	<5	124	<0.5	<5	3.45	1	28	7	70	6.54	3	0.42	<10	1.69	2193	<2	0.03	5	1766	26	0.53	<5	5	85	<5	0.16	<10	<10	89	<10	98	3
122079	<0.2	2.30	<5	98	<0.5	<5	2.81	1	20	8	65	4.91	1	0.32	<10	1.40	1713	<2	0.02	4	1710	28	0.34	<5	4	84	<5	0.12	<10	<10	61	<10	84	3
122080	<0.2	2.75	<5	98	<0.5	<5	4.37	1	20	11	51	5.69	1	0.31	<10	1.74	2034	<2	0.03	4	1648	22	0.13	<5	5	136	<5	0.12	<10	10	81	<10	97	3
122081	1.2	2.32	14	71	<0.5	<5	3.98	2	19	14	118	5.19	1	0.24	<10	1.35	2249	21	0.02	3	1496	149	0.39	<5	4	106	<5	0.12	<10	<10	60	<10	156	4
122082	<0.2	2.58	8	100	<0.5	<5	3.50	1	24	6	71	5.59	1	0.33	<10	1.57	1966	<2	0.02	4	1676	35	0.39	<5	5	105	<5	0.14	<10	<10	80	<10	92	3
122083	0.2	2.25	15	190	<0.5	<5	3.00	1	21	9	73	5.34	<1	0.31	<10	1.33	1943	<2	0.02	4	1708	25	0.61	<5	3	79	<5	0.11	<10	<10	61	<10	84	3
122084	0.2	2.56	7	126	<0.5	<5	3.34	1	24	5	88	5.73	<1	0.39	<10	1.43	1927	<2	0.03	4	1642	23	0.49	<5	5	103	<5	0.15	<10	<10	73	<10	93	3
122085	0.3	2.74	19	133	<0.5	<5	4.33	2	26	21	67	6.35	<1	0.26	<10	1.61	2190	<2	0.01	6	1717	74	0.63	<5	4	130	<5	0.10	<10	12	68	<10	91	3
122086	0.5	2.43	123	100	<0.5	<5	4.45	4	22	7	70	6.00	<1	0.36	<10	1.31	2371	<2	0.01	3	1636	46	1.14	<5	3	121	<5	0.08	<10	<10	68	<10	100	3
122087	0.9	2.04	1516	76	<0.5	<5	5.02	37	19	8	85	5.56	<1	0.28	<10	1.09	2370	<2	0.01	3	1568	96	1.30	<5	3	130	<5	0.04	<10	<10	58	<10	261	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3671RJ

Date : Oct-28-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 34-a

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122088	0.3	2.46	40	105	<0.5	<5	4.50	2	19	9	64	5.90	<1	0.34	<10	1.27	2343	<2	0.01	3	1654	28	0.63	<5	3	133	<5	0.07	<10	<10	77	<10	119	2
122089	0.6	2.44	84	144	<0.5	<5	5.06	3	20	11	66	5.35	<1	0.43	<10	1.22	2435	<2	0.01	4	1619	70	0.70	<5	4	157	<5	0.03	<10	<10	72	<10	128	2
122090	0.9	2.15	109	111	<0.5	6	3.67	6	17	8	68	5.81	<1	0.32	<10	1.06	1992	<2	0.01	3	1506	59	1.31	<5	3	114	<5	0.01	<10	<10	64	<10	231	2
122091	0.4	2.70	323	133	<0.5	7	4.67	9	19	9	51	6.39	<1	0.41	<10	1.46	2420	<2	0.02	3	1608	29	0.64	<5	4	188	<5	<0.01	<10	<10	75	<10	99	2
122092	1.2	2.08	346	106	<0.5	6	3.98	10	19	11	89	6.43	<1	0.33	<10	1.08	2178	<2	0.01	4	1596	56	2.08	<5	3	130	<5	<0.01	<10	<10	54	<10	159	2
122093	3.4	1.58	200	130	<0.5	5	3.99	27	15	8	158	3.96	<1	0.39	<10	0.95	1918	<2	0.02	3	1464	2567	0.67	<5	3	174	<5	<0.01	<10	<10	38	33	2100	1
122094	0.3	2.32	101	122	<0.5	6	3.24	3	16	8	46	6.15	<1	0.33	<10	1.21	2059	<2	0.02	3	1554	28	0.71	<5	3	142	<5	0.01	<10	<10	64	<10	104	2
122095	<0.2	2.88	22	115	<0.5	5	4.00	2	19	6	34	6.85	<1	0.36	10	1.60	1793	<2	0.03	3	1612	28	0.48	<5	5	167	<5	0.03	<10	11	82	<10	89	3
122096	<0.2	2.11	15	80	<0.5	5	5.11	2	13	9	21	4.82	<1	0.29	<10	1.22	1831	<2	0.02	2	1353	46	0.48	<5	3	179	<5	0.01	<10	<10	49	<10	144	2
122097	<0.2	2.03	1294	83	<0.5	7	9.03	32	14	8	43	5.08	<1	0.29	<10	1.20	3171	<2	0.01	2	1180	25	0.78	<5	3	237	<5	<0.01	<10	12	46	<10	78	2
122098	<0.2	2.09	23	96	<0.5	5	5.37	1	15	9	23	4.69	<1	0.25	<10	1.60	1615	<2	0.03	3	1414	14	0.37	<5	3	239	<5	0.02	<10	<10	63	<10	42	2
122099	<0.2	2.35	25	133	<0.5	5	4.77	2	17	9	33	4.80	<1	0.38	<10	1.62	1671	<2	0.02	3	1450	19	0.44	<5	4	191	<5	0.02	<10	<10	65	<10	43	2
122100	<0.2	0.07	<5	<10	<0.5	8	>15.00	1	1	11	7	0.10	<1	0.02	<10	4.38	106	<2	0.01	1	132	<2	0.03	<5	<1	3810	<5	<0.01	<10	<10	2	<10	71	<1
122101	0.5	2.02	32	115	<0.5	<5	5.95	1	17	7	36	4.78	<1	0.41	<10	1.07	1876	<2	0.02	3	1395	20	0.66	<5	4	178	<5	0.07	<10	<10	71	<10	54	2
122102	0.3	2.40	12	81	<0.5	<5	5.80	1	17	6	40	5.49	<1	0.27	<10	1.72	1696	<2	0.02	2	1367	18	0.22	<5	5	342	<5	0.04	<10	<10	80	<10	80	3
122103	<0.2	2.31	8	92	<0.5	<5	4.62	1	17	7	37	4.71	<1	0.36	<10	1.53	1579	<2	0.03	2	1412	19	0.27	<5	4	193	<5	0.12	<10	<10	69	<10	68	3
122104	0.6	1.58	23	113	<0.5	<5	4.12	2	18	11	48	3.33	<1	0.35	<10	0.97	1408	<2	0.01	3	1449	175	0.44	<5	3	165	<5	0.14	<10	<10	47	<10	126	2
122105	0.2	2.55	19	143	<0.5	<5	3.64	2	22	6	30	6.13	<1	0.41	<10	1.32	2281	<2	0.02	3	1534	21	0.40	<5	7	137	<5	0.17	<10	11	95	<10	131	4
122106	<0.2	1.54	21	102	<0.5	<5	3.78	1	23	7	22	3.36	<1	0.39	10	0.77	1510	4	0.01	5	1486	13	0.21	<5	2	137	<5	0.09	<10	<10	39	<10	73	2
122107	0.2	2.21	19	109	<0.5	<5	4.82	1	19	8	8	4.81	<1	0.55	10	1.00	2151	<2	0.01	3	1446	17	0.44	<5	3	190	<5	0.15	<10	<10	48	<10	78	3
122108	1.5	1.47	49	100	<0.5	<5	4.25	6	19	13	50	3.59	<1	0.42	10	0.62	1941	<2	0.01	3	1465	99	0.64	<5	3	164	<5	0.10	<10	<10	33	10	685	2
122109	0.4	2.14	29	115	<0.5	<5	4.41	2	20	7	41	5.01	<1	0.48	<10	1.03	2070	<2	0.01	3	1459	19	0.64	<5	3	160	<5	0.05	<10	<10	59	<10	98	2
122110	0.3	2.00	18	107	<0.5	<5	4.61	1	16	8	26	4.47	<1	0.41	<10	1.04	1908	<2	0.01	3	1500	17	0.48	<5	3	182	<5	0.02	<10	<10	52	<10	84	2
122111	0.3	2.09	68	159	<0.5	<5	7.07	3	16	10	29	4.05	<1	0.66	<10	0.79	2240	<2	0.05	3	1252	42	1.17	<5	3	178	<5	0.10	<10	<10	50	<10	89	2
122112	0.5	2.64	75	83	<0.5	<5	4.72	3	22	14	77	4.97	<1	0.25	<10	1.24	1728	<2	0.13	3	1421	34	0.79	<5	5	164	<5	0.14	<10	10	95	<10	130	3
122113	0.3	2.55	176	79	<0.5	<5	6.41	5	17	12	80	5.34	<1	0.28	<10	1.48	2122	<2	0.11	3	1327	17	0.88	<5	8	153	<5	0.13	<10	11	121	<10	107	4
122114	0.2	2.75	25	124	<0.5	<5	4.67	2	20	11	32	5.35	<1	0.47	<10	1.57	1749	<2	0.10	3	1481	28	0.86	<5	5	150	<5	0.13	<10	11	91	10	128	3
122115	0.5	2.32	53	105	<0.5	<5	6.32	2	20	7	51	5.53	<1	0.46	<10	1.28	1999	<2	0.05	3	1404	25	1.39	<5	5	168	<5	0.11	<10	<10	77	<10	87	3
122116	0.5	2.24	37	74	<0.5	<5	5.67	2	19	7	42	5.55	<1	0.33	<10	1.30	2099	<2	0.03	4	1481	22	1.04	<5	4	157	<5	0.10	<10	<10	71	<10	89	3
122117	0.2	1.99	22	108	<0.5	<5	6.34	1	17	7	22	4.46	<1	0.49	<10	0.95	2067	<2	0.03	2	1345	12	0.77	<5	4	187	<5	0.13	<10	<10	58	<10	68	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3671RJ

Date : Oct-28-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 34-a

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122118	0.4	1.60	110	118	<0.5	<5	3.03	4	20	11	30	4.86	<1	0.43	<10	0.65	1423	<2	0.01	4	1379	16	1.68	<5	3	106	<5	0.05	<10	<10	41	<10	180	2
122119	0.8	1.65	37	92	<0.5	<5	10.88	2	13	10	31	3.94	<1	0.34	<10	0.94	3275	<2	0.02	2	1022	12	0.64	<5	3	322	<5	0.08	<10	<10	35	<10	61	2
122120	0.3	2.09	9	97	<0.5	<5	3.13	1	18	9	32	5.00	<1	0.31	<10	1.27	1838	<2	0.02	3	1379	18	0.36	<5	3	129	<5	0.03	<10	<10	53	<10	97	2
122121	0.3	2.24	11	132	<0.5	<5	3.47	1	19	10	41	5.34	<1	0.42	10	1.36	1771	<2	0.02	4	1423	16	0.31	<5	4	155	<5	0.01	<10	<10	65	<10	99	2
122122	<0.2	2.04	13	88	<0.5	5	4.05	1	16	14	41	4.94	3	0.27	<10	1.13	1719	<2	0.03	9	1491	14	0.35	<5	4	175	<5	0.01	<10	<10	89	<10	73	2
122123	<0.2	2.26	9	83	<0.5	5	3.47	1	18	13	31	5.41	1	0.27	<10	1.40	1777	<2	0.02	4	1475	16	0.36	<5	4	151	<5	0.02	<10	<10	78	<10	80	2
122124	<0.2	2.14	23	144	<0.5	6	3.76	1	20	11	20	5.18	<1	0.27	<10	1.35	1794	<2	0.02	4	1426	17	0.47	<5	3	141	<5	0.01	<10	<10	66	<10	67	2
122125	>200.0	0.58	583	181	<0.5	111	0.52	23	7	22	7448	2.09	7	0.15	<10	0.57	275	571	0.03	5	468	896	1.13	1716	1	75	<5	0.05	<10	<10	17	<10	896	2
122126	0.8	2.25	29	88	<0.5	7	5.46	2	16	8	44	5.12	1	0.32	<10	1.33	2082	<2	0.02	3	1445	15	0.54	<5	3	183	<5	0.01	<10	<10	61	<10	72	2
122127	0.7	1.94	26	95	<0.5	6	2.66	1	15	15	21	4.69	<1	0.33	<10	1.13	1407	<2	0.02	4	1333	18	0.70	<5	3	110	<5	0.01	<10	<10	48	<10	62	2
122128	0.6	1.91	52	194	<0.5	7	3.37	2	17	9	21	4.91	<1	0.41	<10	0.87	1452	<2	0.01	4	1493	17	0.83	<5	3	111	<5	0.01	<10	<10	56	<10	62	2
122129	<0.2	0.60	88	86	<0.5	<5	6.19	3	9	42	12	2.13	<1	0.24	<10	0.21	1547	<2	0.01	3	654	7	0.97	<5	1	184	<5	<0.01	<10	<10	13	<10	45	1
122130	0.2	2.05	34	98	<0.5	7	4.73	3	17	14	36	5.16	<1	0.34	<10	1.23	1856	<2	0.01	6	1441	14	0.55	<5	4	128	<5	<0.01	<10	<10	59	<10	229	2
122131	0.5	1.83	45	140	<0.5	6	3.91	2	16	11	28	4.86	<1	0.28	<10	1.12	2109	<2	0.01	3	1574	18	0.96	<5	3	165	<5	0.01	<10	<10	52	<10	103	2
122132	1.4	1.99	182	114	<0.5	7	1.71	6	18	13	12	6.39	<1	0.28	<10	1.34	2314	<2	0.01	3	1324	32	2.64	<5	2	91	<5	<0.01	<10	<10	58	<10	109	2
122133	1.3	1.92	120	88	<0.5	7	6.18	6	15	19	11	5.49	<1	0.18	<10	1.30	3287	<2	0.01	3	1037	32	1.90	<5	2	181	<5	<0.01	<10	14	52	<10	319	2
122134	0.7	2.05	95	95	<0.5	7	4.18	5	15	13	24	5.47	<1	0.29	<10	1.31	2231	<2	0.01	3	1264	38	1.30	<5	3	176	<5	<0.01	<10	<10	54	<10	190	2
122135	<0.2	2.19	17	61	<0.5	7	6.18	1	17	16	32	5.15	<1	0.23	<10	1.51	2517	<2	0.01	5	1370	14	0.44	<5	4	169	<5	<0.01	<10	<10	65	<10	75	2
122136	<0.2	2.28	26	87	<0.5	7	5.29	2	18	13	30	5.29	<1	0.30	<10	1.45	2257	<2	0.02	4	1443	17	0.68	<5	4	186	<5	0.01	<10	<10	70	<10	75	2
122137	<0.2	1.89	28	143	<0.5	6	4.89	1	16	10	19	4.74	<1	0.25	<10	1.19	1973	<2	0.01	3	1445	15	0.80	<5	3	152	<5	0.01	<10	<10	62	<10	57	2
122181	0.2	1.78	26	126	<0.5	<5	3.52	1	14	12	22	3.66	<1	0.27	10	0.97	1648	<2	0.02	3	1327	12	0.35	<5	3	116	<5	0.08	<10	<10	33	<10	78	2
122182	0.3	1.90	28	112	<0.5	<5	3.22	2	16	14	21	4.29	<1	0.24	11	0.99	1545	<2	0.03	3	1273	16	0.62	<5	3	116	<5	0.06	<10	<10	38	<10	82	2
122183	0.4	1.68	50	103	<0.5	<5	3.40	2	14	13	19	4.05	<1	0.22	11	0.88	1648	<2	0.02	3	1257	12	0.74	<5	2	127	<5	0.02	<10	<10	31	<10	76	2
122184	1.1	1.41	55	135	<0.5	5	2.17	2	14	14	26	3.70	<1	0.29	<10	0.59	1141	<2	0.01	3	1210	12	1.04	<5	2	60	<5	<0.01	<10	<10	23	<10	77	2
122185	2.4	1.17	138	172	<0.5	5	0.71	4	13	21	30	3.76	<1	0.20	<10	0.51	789	4	0.01	3	809	19	1.23	<5	1	31	<5	<0.01	<10	<10	15	<10	115	2
122186	1.8	1.16	175	140	<0.5	5	1.75	5	13	29	20	3.83	<1	0.22	<10	0.49	970	4	0.01	3	816	15	1.65	<5	2	96	<5	<0.01	<10	<10	14	<10	76	2
122187	1.8	0.78	99	136	<0.5	<5	6.96	3	8	72	14	3.03	<1	0.33	<10	0.30	1747	<2	0.01	3	798	8	2.23	<5	2	252	<5	<0.01	<10	<10	12	<10	64	1
122188	6.3	0.55	177	84	<0.5	<5	2.50	6	11	47	15	4.93	<1	0.28	<10	0.17	766	<2	0.01	3	880	59	4.88	<5	1	106	<5	<0.01	<10	<10	8	18	226	2
122189	2.0	0.81	285	74	<0.5	<5	0.59	8	14	31	14	4.88	<1	0.30	<10	0.29	463	<2	0.01	3	1180	28	4.50	<5	1	24	<5	<0.01	<10	<10	14	<10	97	3
122190	1.6	0.62	255	71	<0.5	5	3.00	7	13	40	8	4.60	<1	0.33	<10	0.18	895	<2	0.01	3	979	21	>5.00	<5	1	83	<5	<0.01	<10	<10	12	<10	53	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3671RJ

Date : Oct-28-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 34-a

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122191	5.1	0.76	469	109	<0.5	<5	1.28	17	12	29	33	3.29	1	0.26	<10	0.30	798	2	0.01	3	1022	548	2.42	<5	1	44	<5	<0.01	<10	<10	12	<10	619	2
122192	3.2	1.07	160	140	<0.5	<5	1.61	10	13	28	48	3.67	<1	0.33	10	0.43	1118	2	0.01	3	1090	89	2.32	<5	2	54	<5	<0.01	<10	<10	17	10	590	2
122193	2.2	0.75	249	79	<0.5	<5	0.51	8	14	45	14	4.89	<1	0.28	<10	0.31	497	<2	0.01	3	931	175	4.38	<5	1	27	<5	<0.01	<10	<10	13	<10	147	3
122194	2.9	0.69	481	62	<0.5	<5	0.57	14	14	37	20	4.74	<1	0.37	<10	0.18	266	<2	0.01	3	1193	138	4.82	<5	1	27	<5	<0.01	<10	<10	11	<10	324	3
122195	4.2	0.29	327	71	<0.5	<5	2.41	14	12	57	12	3.91	1	0.19	<10	0.07	745	3	0.01	3	779	207	4.84	<5	1	83	<5	<0.01	<10	<10	6	13	723	2
122196	2.4	1.13	211	57	<0.5	6	0.84	7	18	43	7	6.42	<1	0.33	<10	0.52	719	<2	0.01	3	1345	63	>5.00	<5	2	37	<5	<0.01	<10	<10	23	<10	144	3
122197	3.5	0.67	563	69	<0.5	<5	1.06	17	17	58	8	4.80	1	0.27	<10	0.29	734	3	0.01	3	1106	262	4.78	<5	1	55	<5	<0.01	<10	<10	14	<10	521	3
122198	56.1	0.73	1212	15	<0.5	6	0.57	611	13	61	1518	8.80	32	0.19	<10	0.34	594	<2	0.01	3	698	>10000	>5.00	33	2	18	<5	<0.01	<10	18	15	914	>10000	5
122199	18.5	0.62	1326	48	<0.5	<5	0.42	129	11	63	635	5.10	7	0.18	<10	0.28	452	8	0.01	3	755	2709	>5.00	22	1	19	<5	<0.01	<10	<10	11	155	>10000	3
122200	<0.2	0.07	10	16	<0.5	9	>15.00	4	1	14	3	0.11	1	0.02	<10	1.87	46	<2	0.01	<1	70	9	0.12	<5	<1	4828	<5	<0.01	<10	<10	1	<10	9	<1
122201	22.1	0.13	340	55	<0.5	<5	1.84	98	4	96	383	4.41	7	0.11	<10	0.03	623	<2	0.01	2	206	7258	>5.00	19	<1	91	<5	<0.01	<10	<10	1	173	>10000	2
122202	1.4	0.52	212	54	<0.5	<5	0.79	7	13	38	13	4.76	<1	0.31	<10	0.15	274	<2	0.01	4	365	103	4.97	<5	1	59	<5	<0.01	<10	<10	8	<10	195	3
122203	4.5	0.55	264	91	<0.5	<5	0.45	11	14	67	56	4.40	<1	0.26	<10	0.20	320	14	0.01	5	911	153	4.22	<5	1	24	<5	<0.01	<10	<10	10	<10	454	2
122204	4.0	1.22	366	63	<0.5	5	0.90	11	19	26	32	5.67	<1	0.39	<10	0.58	910	<2	0.01	5	2129	54	4.18	<5	3	48	<5	<0.01	<10	<10	24	<10	217	3
122205	1.1	0.45	68	113	<0.5	<5	3.84	3	9	114	7	3.94	<1	0.18	<10	0.97	2368	2	0.01	3	937	29	1.79	<5	2	303	<5	<0.01	<10	<10	11	<10	93	2
122206	0.7	0.63	87	378	<0.5	<5	1.81	3	7	142	7	2.66	<1	0.19	<10	0.58	1133	<2	0.01	3	769	12	0.75	<5	2	123	<5	<0.01	<10	<10	12	<10	71	1
122207	4.2	1.09	296	117	<0.5	<5	0.66	9	19	100	23	5.10	<1	0.27	<10	0.54	676	3	0.01	5	1322	95	2.90	<5	3	39	<5	<0.01	<10	<10	21	<10	165	3
122208	16.6	0.29	336	80	<0.5	<5	2.25	27	8	92	178	3.81	<1	0.21	<10	0.07	771	9	0.01	3	321	2367	4.28	9	1	87	<5	<0.01	<10	<10	5	28	1720	2
122209	3.5	0.64	488	147	<0.5	<5	0.60	12	11	91	34	2.97	<1	0.28	<10	0.17	332	4	0.01	4	926	72	2.20	<5	1	33	<5	<0.01	<10	<10	11	<10	104	2
122210	11.0	0.74	260	123	<0.5	5	0.75	19	13	59	60	3.71	<1	0.29	<10	0.25	433	5	0.01	4	975	1167	3.05	<5	1	39	<5	<0.01	<10	<10	14	23	1647	2
122211	15.9	0.93	510	147	<0.5	<5	0.69	23	15	45	79	3.97	1	0.26	<10	0.39	584	3	0.01	5	1150	351	2.64	<5	2	36	<5	<0.01	<10	<10	19	21	1445	2
122212	1.3	2.21	109	204	<0.5	5	1.37	4	21	25	46	5.26	<1	0.33	11	1.18	1613	<2	0.01	6	1690	38	0.57	<5	4	55	<5	<0.01	<10	<10	44	<10	124	2
122213	1.5	1.80	369	146	<0.5	5	0.82	9	21	31	28	5.04	<1	0.24	12	1.03	1167	<2	0.01	4	1430	21	0.91	<5	4	40	<5	<0.01	<10	<10	41	<10	96	2
122214	1.7	0.53	173	181	<0.5	<5	1.42	5	11	45	11	2.95	<1	0.29	<10	0.33	866	<2	0.01	3	948	33	1.99	<5	2	79	<5	<0.01	<10	<10	12	<10	50	2
122215	2.7	0.55	207	147	<0.5	<5	0.89	6	12	56	16	3.34	<1	0.26	<10	0.27	498	5	0.01	3	981	44	2.57	<5	1	43	<5	<0.01	<10	<10	13	<10	83	2
122216	2.7	1.02	315	228	<0.5	<5	0.83	8	12	55	17	3.39	<1	0.31	10	0.43	695	<2	0.02	3	1030	26	1.67	<5	2	30	<5	<0.01	<10	<10	25	<10	60	2
122217	2.4	0.90	143	166	<0.5	<5	0.99	4	9	60	21	2.78	<1	0.23	<10	0.41	734	<2	0.01	3	918	29	1.09	<5	2	40	<5	<0.01	<10	<10	23	<10	84	2
122218	5.6	0.53	325	159	<0.5	<5	3.29	8	12	50	23	3.13	<1	0.26	<10	0.18	1126	3	0.01	3	770	33	2.99	<5	2	126	<5	<0.01	<10	<10	15	<10	44	2
122219	3.5	0.39	414	65	<0.5	<5	1.86	11	18	57	22	3.99	<1	0.28	<10	0.10	544	9	0.01	4	1090	53	4.13	<5	2	83	<5	0.01	<10	<10	11	<10	73	2
122220	2.9	1.51	236	80	<0.5	5	3.32	7	29	21	92	6.66	<1	0.36	<10	0.90	1438	<2	0.01	3	2050	77	>5.00	<5	4	160	<5	0.01	<10	11	39	<10	134	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3671RJ

Date : Oct-28-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 34-a

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122221	1.5	1.24	216	164	<0.5	5	3.29	6	23	31	33	4.59	<1	0.32	<10	0.67	1418	2	0.01	4	1480	40	3.08	<5	3	139	<5	<0.01	<10	<10	37	<10	59	2
122222	2.1	1.17	202	195	<0.5	5	5.80	6	33	25	49	4.33	<1	0.37	<10	0.55	1695	2	0.01	3	1420	75	2.78	<5	3	236	<5	0.01	<10	<10	33	<10	77	2
122223	1.7	1.44	176	169	<0.5	5	5.00	5	27	23	53	5.29	<1	0.32	<10	0.77	1587	<2	0.01	3	1540	20	3.00	<5	3	200	<5	0.02	<10	<10	42	<10	52	3
122224	1.6	1.50	187	196	<0.5	<5	5.45	5	16	23	47	5.36	<1	0.39	<10	0.77	1831	<2	0.01	3	1500	24	3.14	<5	3	227	<5	0.02	<10	<10	43	<10	49	3
122225	0.3	1.14	7601	25	<0.5	17	6.95	183	189	16	74	4.10	<1	0.06	13	0.26	831	17	0.10	35	1450	16	1.47	<5	2	105	<5	0.08	<10	<10	45	<10	113	13
122226	1.3	1.22	136	175	<0.5	<5	5.40	4	15	33	33	4.22	<1	0.29	<10	0.66	1856	2	0.01	3	1260	13	2.28	<5	3	245	<5	0.04	<10	<10	32	<10	47	2
122227	1.9	1.36	196	194	<0.5	<5	4.66	5	22	21	48	4.91	<1	0.44	<10	0.67	1609	<2	0.01	3	1550	32	3.31	<5	3	210	<5	0.04	<10	<10	39	<10	56	2
122228	1.5	1.07	158	174	<0.5	<5	4.23	4	17	25	46	4.31	<1	0.33	<10	0.56	1452	2	0.01	3	1290	20	2.99	<5	3	171	<5	0.02	<10	<10	28	<10	51	2
122229	1.9	1.80	139	183	<0.5	<5	4.52	4	24	22	51	5.84	<1	0.38	<10	1.00	2118	<2	0.01	3	1430	23	2.70	<5	3	239	<5	0.06	<10	<10	54	<10	72	3
122230	4.6	1.00	230	140	<0.5	<5	2.69	6	21	32	44	4.36	<1	0.34	<10	0.49	1154	<2	0.01	3	1240	30	3.07	<5	2	128	<5	0.04	<10	<10	27	<10	84	2
122231	80.0	0.19	489	97	<0.5	<5	2.29	37	7	80	68	2.95	5	0.17	<10	0.03	567	3	0.01	3	420	1037	3.37	21	1	127	<5	<0.01	<10	<10	6	55	3715	2
122232	169.0	0.13	471	79	<0.5	<5	1.29	55	4	137	213	3.66	5	0.07	<10	0.06	484	<2	0.01	4	165	3913	4.16	114	<1	90	<5	<0.01	<10	<10	2	96	6285	2
122233	21.4	1.46	425	142	<0.5	9	1.08	17	24	30	46	6.10	<1	0.32	<10	1.10	1975	<2	0.01	4	2165	495	4.24	<5	2	62	<5	0.01	<10	<10	48	19	953	3
122234	2.9	1.94	150	167	<0.5	6	1.96	5	23	30	41	6.01	2	0.31	<10	1.34	2242	<2	0.02	3	2198	77	1.56	<5	2	96	<5	0.01	<10	11	51	<10	197	2
122235	1.6	1.97	97	188	<0.5	5	1.99	4	17	16	41	4.45	1	0.39	<10	0.94	1532	<2	0.02	2	1868	45	0.63	<5	2	92	<5	<0.01	<10	<10	49	<10	107	2
122236	1.0	1.99	163	158	<0.5	5	3.96	5	20	19	39	4.84	<1	0.33	<10	1.04	1934	<2	0.02	2	1751	26	1.07	<5	2	180	<5	0.01	<10	<10	42	<10	105	2
122237	0.7	2.09	50	179	<0.5	5	4.73	2	18	12	41	4.49	<1	0.37	10	1.08	2003	<2	0.02	2	1749	24	0.44	<5	2	208	<5	0.01	<10	<10	43	<10	81	2
122238	0.5	1.87	170	169	<0.5	6	5.59	5	17	20	26	4.62	<1	0.36	<10	0.97	1983	<2	0.02	2	1766	39	1.17	<5	2	221	<5	0.01	<10	<10	45	<10	79	2
122239	0.8	2.09	68	181	<0.5	6	3.76	3	20	16	43	4.73	<1	0.37	<10	1.21	1843	<2	0.02	4	1779	35	0.78	<5	3	163	<5	0.01	<10	<10	52	<10	113	2
122240	0.8	2.02	70	151	<0.5	6	3.66	4	18	21	38	4.96	<1	0.32	<10	1.08	1733	<2	0.02	5	1888	24	0.87	<5	2	146	<5	0.01	<10	<10	49	<10	151	2
122241	7.1	1.82	99	161	<0.5	5	4.51	6	17	19	53	4.57	<1	0.36	<10	0.97	2062	2	0.02	3	1609	80	1.17	<5	2	165	<5	<0.01	<10	<10	40	<10	410	2
122242	1.6	2.05	152	184	<0.5	5	4.04	5	18	19	41	4.82	<1	0.42	<10	1.06	1785	<2	0.02	2	1892	32	1.02	<5	3	137	<5	0.01	<10	<10	49	<10	120	2
122243	3.4	1.88	95	150	<0.5	6	3.57	4	19	29	42	4.97	<1	0.32	<10	1.04	1766	<2	0.02	2	1847	43	1.30	<5	2	165	<5	0.01	<10	<10	43	<10	125	2
122244	2.9	1.76	210	167	<0.5	5	2.42	6	20	18	33	5.33	<1	0.37	<10	1.02	1457	<2	0.02	2	1913	34	2.39	<5	2	77	<5	0.01	<10	<10	41	<10	97	3
122245	2.2	1.70	290	146	<0.5	5	3.77	8	19	26	39	5.54	<1	0.30	<10	0.98	1820	<2	0.01	2	1700	24	2.53	<5	2	104	<5	0.01	<10	<10	39	<10	106	2
122246	1.3	1.97	117	180	<0.5	<5	2.52	4	21	17	41	5.24	<1	0.35	<10	1.13	1714	<2	0.02	2	1880	24	1.57	<5	2	84	<5	0.02	<10	<10	46	<10	96	2
122247	1.0	1.65	94	161	<0.5	<5	3.99	3	18	21	34	4.71	<1	0.31	<10	0.99	1960	<2	0.02	2	1828	22	1.80	<5	2	134	<5	0.03	<10	<10	41	<10	90	2
122248	0.8	1.25	82	148	<0.5	<5	3.14	3	13	16	19	3.45	<1	0.27	<10	0.70	1412	<2	0.01	2	1241	21	1.45	<5	2	101	<5	0.01	<10	<10	30	<10	86	2
122249	1.9	1.61	144	174	<0.5	6	4.43	6	18	20	33	4.88	<1	0.30	<10	0.88	1944	<2	0.02	2	1634	31	2.08	<5	2	126	<5	0.01	<10	<10	37	<10	236	2
122250	<0.2	0.05	<5	12	<0.5	10	>15.00	<1	1	8	2	0.07	<1	0.02	<10	2.03	45	<2	0.01	<1	77	<2	0.06	<5	<1	4725	<5	<0.01	<10	<10	1	<10	3	<1

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3671RJ

Date : Oct-28-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 34-a

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122251	1.0	1.59	79	158	<0.5	<5	3.93	3	15	22	28	3.74	<1	0.30	<10	0.84	1678	<2	0.01	2	1616	18	0.56	<5	2	134	<5	<0.01	<10	<10	38	<10	99	2
122252	0.9	1.33	438	183	<0.5	<5	5.01	11	12	24	25	3.39	<1	0.41	<10	0.63	1382	2	0.01	2	1530	17	1.14	<5	2	288	<5	<0.01	<10	<10	33	<10	54	2
122253	1.6	1.40	526	169	<0.5	<5	2.52	14	15	24	45	4.09	<1	0.34	<10	0.69	1284	<2	0.01	4	1397	50	1.49	<5	2	89	<5	<0.01	<10	<10	32	<10	209	2
122254	8.5	0.81	99	193	<0.5	<5	7.15	4	9	62	23	2.25	<1	0.21	<10	0.41	2221	<2	0.01	3	742	40	0.77	<5	1	593	<5	<0.01	<10	<10	12	<10	176	1
122255	5.5	1.51	189	145	<0.5	<5	1.87	6	20	16	60	4.02	<1	0.37	<10	0.67	1153	<2	0.01	3	1646	35	1.08	<5	2	55	<5	<0.01	<10	<10	35	<10	110	2
122256	3.7	1.20	235	147	<0.5	<5	4.24	7	17	18	42	4.19	<1	0.39	<10	0.50	1463	<2	0.01	3	1420	41	2.53	<5	2	130	<5	<0.01	<10	<10	27	<10	77	2
122257	3.5	1.35	323	112	<0.5	<5	4.51	9	18	19	34	4.49	<1	0.28	<10	0.65	1615	<2	0.01	3	1423	33	2.27	<5	2	136	<5	<0.01	<10	<10	31	<10	123	2
122258	3.4	1.27	268	138	<0.5	<5	4.43	7	16	18	33	3.97	<1	0.37	<10	0.52	1554	<2	0.01	2	1434	24	2.07	<5	2	165	<5	<0.01	<10	<10	30	<10	72	2
122259	3.0	1.27	125	114	<0.5	<5	5.66	4	15	13	33	3.92	<1	0.31	<10	0.57	1801	<2	0.01	2	1472	24	1.79	<5	2	163	<5	<0.01	<10	<10	30	<10	77	2
122260	3.0	1.48	253	131	<0.5	<5	4.35	7	20	12	56	4.18	<1	0.35	<10	0.65	1575	3	0.01	2	1426	31	1.49	<5	2	132	<5	<0.01	<10	<10	36	<10	100	2
122261	2.1	0.84	470	85	<0.5	<5	3.76	12	13	20	30	3.48	<1	0.25	<10	0.37	1135	<2	0.01	2	1127	22	2.39	<5	1	85	<5	<0.01	<10	<10	22	<10	87	2
122262	3.8	0.63	344	140	<0.5	<5	5.96	13	11	30	42	3.48	<1	0.29	<10	0.23	1526	2	0.01	2	938	328	3.20	<5	1	198	<5	<0.01	<10	<10	14	<10	637	2
122263	5.2	0.98	262	99	<0.5	6	7.83	13	14	18	95	4.63	<1	0.25	<10	0.50	2164	<2	0.01	2	1229	621	3.71	<5	2	281	<5	<0.01	<10	<10	24	13	850	2
122264	2.2	1.44	109	117	<0.5	5	4.21	4	16	15	36	4.72	<1	0.31	<10	0.72	1362	<2	0.01	3	1368	30	2.55	<5	2	134	<5	<0.01	<10	<10	36	<10	89	2
122265	1.7	1.38	143	83	<0.5	5	7.03	5	14	20	35	4.93	<1	0.29	<10	0.73	1828	<2	0.01	2	1243	29	3.14	<5	2	212	<5	<0.01	<10	<10	32	<10	109	2
122266	1.6	1.35	169	100	<0.5	5	7.15	5	15	16	34	5.44	<1	0.32	<10	0.66	1866	<2	0.01	2	1249	26	3.73	<5	2	205	<5	<0.01	<10	<10	31	<10	101	3
122267	2.2	1.59	191	92	<0.5	6	4.52	6	18	19	48	7.13	<1	0.25	<10	0.83	1597	<2	0.01	3	1320	31	>5.00	<5	2	118	<5	<0.01	<10	14	43	<10	91	3
122268	2.0	1.41	466	82	<0.5	6	2.97	12	16	16	31	7.43	<1	0.30	<10	0.73	1163	<2	0.01	2	1382	25	>5.00	<5	2	85	<5	<0.01	<10	14	31	<10	97	4
122269	2.1	0.67	1033	69	<0.5	<5	5.02	26	12	41	22	4.18	<1	0.23	<10	0.29	1297	<2	0.01	2	800	25	4.09	<5	2	124	<5	<0.01	<10	<10	17	<10	96	2
122270	3.1	0.70	545	70	<0.5	<5	2.39	14	12	31	26	3.30	<1	0.24	<10	0.32	773	2	0.01	3	742	27	2.53	<5	2	55	<5	<0.01	<10	<10	20	<10	92	2
122271	1.7	0.82	2666	67	<0.5	<5	3.01	64	15	29	30	3.66	<1	0.22	<10	0.43	908	<2	0.01	3	902	18	2.48	<5	1	62	<5	0.01	<10	<10	19	<10	96	2
122272	0.9	0.97	1173	94	<0.5	<5	4.43	28	15	19	32	3.72	<1	0.30	<10	0.48	1165	<2	0.02	3	1087	14	2.63	<5	2	118	<5	0.02	<10	<10	21	<10	70	2
122273	1.9	1.14	487	82	<0.5	<5	4.21	13	22	25	75	5.19	<1	0.26	<10	0.59	1122	<2	0.02	4	1238	18	3.79	<5	2	108	<5	0.02	<10	<10	30	<10	63	3
122274	2.0	0.95	2573	95	<0.5	<5	4.73	61	17	22	50	3.85	<1	0.35	<10	0.43	1224	<2	0.02	4	1182	30	2.93	<5	3	116	<5	0.01	<10	<10	28	<10	156	2
122275	<0.2	0.07	<5	11	<0.5	9	>15.00	<1	1	9	2	0.06	<1	0.02	<10	1.83	34	<2	0.01	<1	67	<2	0.05	<5	<1	4492	<5	<0.01	<10	<10	2	<10	3	<1
122276	1.3	1.70	108	217	<0.5	<5	4.55	3	19	28	51	4.47	<1	0.36	<10	0.98	1453	<2	0.04	6	1324	25	1.77	<5	4	122	<5	0.02	<10	<10	61	<10	105	3
122277	5.5	1.76	392	93	<0.5	8	8.52	10	37	14	89	6.95	<1	0.26	<10	1.12	1968	<2	0.02	5	1508	39	4.65	<5	4	543	<5	0.02	<10	12	63	<10	110	3
122278	4.0	1.54	333	93	<0.5	7	3.17	9	27	28	64	7.25	<1	0.36	<10	0.73	1365	<2	0.02	5	1915	29	>5.00	<5	4	84	<5	0.01	<10	11	62	<10	106	4
122279	3.0	1.68	197	90	<0.5	7	7.10	6	21	18	53	6.07	<1	0.27	<10	0.90	2233	<2	0.03	3	1686	22	3.52	<5	4	146	<5	<0.01	<10	<10	62	<10	135	3
122280	4.6	1.09	143	90	<0.5	8	5.67	7	52	26	46	6.16	<1	0.36	<10	0.46	1692	8	0.02	9	1218	29	>5.00	<5	3	142	<5	<0.01	<10	<10	33	10	646	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment 34-a

Sample type: core

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : 8V3671RJ

Date : Oct-28-08

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122281	1.1	1.91	75	94	<0.5	5	4.45	3	20	17	42	5.34	<1	0.27	<10	1.05	1608	<2	0.02	4	1863	17	1.64	<5	4	129	<5	0.01	<10	<10	70	<10	123	3
122282	1.1	2.16	77	100	<0.5	6	6.65	3	20	16	53	5.15	<1	0.30	<10	1.17	2067	<2	0.02	4	1570	17	0.99	<5	4	169	<5	0.01	<10	<10	67	<10	141	2
122283	1.0	2.34	65	93	<0.5	7	4.88	3	21	16	41	6.04	<1	0.26	<10	1.24	2023	<2	0.02	3	1749	19	0.97	<5	4	131	<5	0.01	<10	<10	72	<10	161	3
122284	1.8	2.41	95	110	<0.5	8	4.31	4	31	15	70	6.66	<1	0.34	<10	1.16	2074	<2	0.02	5	1425	26	1.68	<5	4	107	<5	<0.01	<10	10	91	<10	310	3
122285	3.9	1.82	324	83	<0.5	6	3.16	10	38	23	61	6.69	1	0.27	<10	0.88	1587	5	0.02	6	1231	30	3.24	<5	3	69	<5	<0.01	<10	10	65	<10	321	3
122286	2.9	2.20	222	106	<0.5	6	3.54	6	29	19	57	6.40	<1	0.37	<10	1.04	1891	2	0.02	4	1580	27	1.91	<5	4	87	<5	<0.01	<10	<10	81	<10	141	3
122287	2.4	2.13	328	85	<0.5	6	3.40	9	28	19	60	5.85	<1	0.27	<10	1.02	1908	<2	0.02	4	1248	31	1.14	<5	4	92	<5	<0.01	<10	<10	80	<10	174	3
122288	2.8	2.38	128	93	<0.5	7	5.76	4	26	14	55	6.77	<1	0.31	<10	1.16	2368	<2	0.02	4	1551	27	1.81	<5	4	139	<5	<0.01	<10	14	93	<10	137	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Quality Assaying for over 25 Years

Assay Certificate

8V-3672-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment34-B**
Attn: **Sue Deane**

Nov-04-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122411	0.46	0.44	2.9
122412	0.42		4.9
122413	0.21		3.2
122414	0.33		2.4
122415	0.29		3.8
122416	0.29		5.5
122417	0.39		5.9
122418	0.30		3.2
122419	0.35		5.0
122420	0.33	0.32	6.8
122421	0.41		6.7
122422	0.32		2.2
122423	0.59		1.7
122424	0.23		1.8
122425	0.01		<0.1
122426	0.22		2.1
122427	0.44		2.9
122428	0.23		3.4
122429	0.26		2.3
122430	0.18	0.18	2.0
122431	0.46		1.9
122432	0.42		2.7
*0211	2.11		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3672-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment34-B**
Attn: **Sue Deane**

Nov-04-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122433	0.20	0.20	1.8
122434	0.37		3.4
122435	0.47		3.7
122436	0.08		1.5
122437	0.24		1.2
122438	0.06		1.6
122439	1.81		2.6
122440	0.35		2.3
122441	0.18		2.2
122442	0.07	0.07	2.0
122443	0.08		1.5
122444	0.11		3.3
122445	0.66		1.8
122446	0.36		0.9
122447	0.29		5.6
122448	0.14		3.8
122449	0.09		2.3
122450	<0.01		<0.1
122501	0.13		2.4
122502	0.08	0.08	3.9
122503	0.35		5.8
122504	0.35		4.4
*0211	2.13		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3672-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment34-B**
Attn: **Sue Deane**

Nov-04-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122505	0.08	0.08	4.7
122506	0.13		3.9
122507	0.45		3.9
122508	0.12		2.6
122509	0.07		2.9
122510	0.04		2.3
122511	0.58		3.9
122512	0.03		0.8
122513	0.17		8.8
122514	0.21	0.23	11.4
122515	0.09		3.4
122516	0.14		5.5
122517	0.17		2.9
122518	0.15		3.6
122519	0.20		4.2
122520	0.06		2.7
122521	0.17		7.5
122522	0.47		5.2
122523	0.14		2.8
122524	0.31	0.30	5.4
122525	<0.01		<0.1
122526	0.14		2.6
*0211	2.24		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3672-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment34-B**
Attn: **Sue Deane**

Nov-04-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122527	0.12	0.13	1.5
122528	0.51		3.7
122529	0.35		3.3
122530	0.42		4.8
122531	0.39		2.4
122532	0.54		2.3
122533	0.35		3.2
122534	0.41		5.6
122535	0.41		3.3
122536	0.52	0.50	2.8
122537	0.10		5.2
122538	0.25		1.7
122539	0.20		2.6
122540	0.48		3.0
122541	0.49		3.1
122542	0.12		1.9
122543	0.47		3.8
122544	0.27		4.0
122545	0.17		3.8
122546	0.09	0.10	2.5
122547	0.09		3.1
122653	0.22		6.2
*0211	2.22		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3672-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment34-B**
Attn: **Sue Deane**

Nov-04-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122654	0.45	0.39	11.0
122655	1.29		6.8
122656	0.22		1.2
122657	0.38		7.0
122658	0.14		6.2
122659	0.10		2.2
122660	0.09		2.7
122661	0.08		2.9
122662	0.11		2.6
122663	0.12	0.11	3.8
122664	0.13		2.9
122665	0.06		2.2
122666	0.05		1.7
122667	0.24		2.4
122668	0.49		4.2
122669	0.33		6.1
122670	0.49		5.5
122671	0.38		1.9
122672	0.17		2.9
122673	0.20	0.19	2.7
122674	0.07		1.8
122675	0.15		3.4
*0211	2.22		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3672-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment34-B**
Attn: **Sue Deane**

Nov-04-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122676	0.11	0.11	1.5
122677	0.09		2.7
122678	0.03		1.2
122679	0.11		2.6
122680	0.33		5.3
122681	0.26		3.0
122682	0.25		3.5
122683	0.23		2.7
122684	0.03		2.0
122685	0.03	0.05	1.3
122686	0.09		1.3
122687	0.29		2.2
122688	0.10		1.2
122689	0.02		1.1
122690	0.05		1.6
122691	0.33		1.9
122692	0.55		2.5
122693	0.36		16.3
122694	0.16		7.5
122695	0.08	0.08	6.2
122696	0.03		3.7
122697	0.03		3.8
*0211	2.03		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3672-RA7

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment34-B**
Attn: **Sue Deane**

Nov-04-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122698	0.08	0.08	5.2
122699	0.03		5.6
122700	0.03		2.2
122701	<0.01		1.2
122702	0.02		2.0
122703	0.02		3.5
122704	<0.01		1.6
122705	0.01		1.9
122706	<0.01		1.7
122707	0.03	0.04	2.9
122708	0.02		2.5
122709	0.31		4.3
122710	0.03		2.4
122711	0.13		4.8
122712	0.13		3.0
122713	0.07		5.2
122714	0.05		2.2
122715	0.16		5.1
122716	0.32		3.2
122717	0.15	0.12	2.1
122718	0.16		3.0
122719	0.12		2.1
*0211	2.21		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3672-RA8

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment34-B**
Attn: **Sue Deane**

Nov-04-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122720	0.06	0.07	1.2
122721	0.05		1.8
122722	0.11		1.5
122723	0.09		3.0
122724	0.06		1.3
122725	0.04		1.1
122726	0.08		1.6
122727	0.09		1.3
122728	0.14		1.7
122729	0.04	0.06	1.4
122730	0.09		1.4
122731	0.10		1.6
122732	0.02		1.8
122733	0.06		1.1
122734	0.38		3.0
122735	0.22		1.7
122736	0.80		1.0
122737	0.84		1.2
122738	0.34		1.6
122739	0.62	0.63	1.2
122740	0.66		1.7
122741	0.27		1.5
*0211	2.10		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3672-RA9

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment34-B**
Attn: **Sue Deane**

Nov-04-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122742	0.06	0.05	2.2
122743	0.05		1.8
122744	0.05		1.2
122745	0.01		0.9
122746	0.05		1.2
122747	0.03		1.4
122748	0.01		0.6
122749	0.02		0.6
122750	0.03		0.4
122751	<0.01	0.02	0.5
122752	0.02		1.1
122753	0.19		1.8
122754	0.37		1.6
122755	0.05		1.5
122756	0.23		2.3
122757	0.06		0.8
122758	0.13		1.1
122759	0.04		1.1
122760	0.06		1.1
122761	0.06	0.08	0.9
122762	0.16		1.8
122763	0.42		1.9
*0211	2.13		
*BLANK	<0.01		

Certified by _____

Quality Assaying for over 25 Years

Assay Certificate

8V-3672-RA10

Company: **Ascot Resources Ltd**
Project: **Dilworth/Shipment34-B**
Attn: **Sue Deane**

Nov-04-08

We hereby certify the following assay of 6 core samples
submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122764	0.35	0.37	2.5
122765	0.71		3.9
122766	0.48		2.4
122767	0.40		2.7
122768	0.27		1.3
122769	0.49		1.4
*0211	2.12		
*BLANK	<0.01		

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3672RJ**

Date : Nov-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment34-B

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122411	2.9	2.36	28	139	<0.5	<5	2.93	2	18	21	283	4.77	<1	0.47	<10	1.13	1700	62	0.01	1	1437	27	0.49	<5	6	42	<5	0.11	<10	<10	77	<10	210	3
122412	4.9	0.96	118	78	<0.5	<5	1.92	4	10	51	117	3.11	<1	0.25	<10	0.38	1032	25	0.01	3	927	31	1.05	<5	2	44	<5	0.01	<10	<10	21	<10	161	1
122413	3.2	1.59	68	122	<0.5	<5	3.91	3	12	26	143	4.14	1	0.31	<10	0.82	1668	23	0.02	2	1180	34	1.03	<5	4	109	<5	0.04	<10	<10	51	<10	146	3
122414	2.4	2.09	66	81	<0.5	5	4.05	3	16	18	169	5.37	<1	0.20	<10	1.22	1860	38	0.02	2	1425	25	0.79	<5	5	105	<5	0.04	<10	<10	73	<10	213	3
122415	3.8	2.14	59	111	<0.5	<5	4.07	3	17	19	299	5.42	<1	0.28	<10	1.10	2146	47	0.03	1	1563	30	0.92	<5	4	185	<5	0.08	<10	<10	75	<10	235	3
122416	5.5	1.54	198	85	<0.5	<5	4.54	7	15	22	342	5.09	<1	0.28	<10	0.88	2062	23	0.01	1	1595	29	2.40	<5	3	120	<5	0.02	<10	<10	45	<10	244	2
122417	5.9	1.48	275	100	<0.5	<5	5.09	9	13	19	369	4.77	<1	0.32	<10	0.80	2202	79	0.02	1	1475	20	2.18	<5	3	146	<5	0.01	<10	<10	42	<10	234	2
122418	3.2	1.35	230	78	<0.5	6	5.79	8	15	22	186	4.89	<1	0.26	<10	0.74	2210	60	0.01	1	1457	26	2.65	<5	2	139	<5	0.01	<10	<10	37	<10	210	2
122419	5.0	1.84	149	76	<0.5	<5	4.39	6	16	24	364	5.50	<1	0.25	<10	0.98	2154	59	0.03	1	1521	24	1.75	<5	3	96	<5	0.02	<10	<10	60	<10	241	2
122420	6.8	1.11	209	82	<0.5	<5	7.70	8	14	30	409	4.32	<1	0.26	<10	0.57	1906	120	0.01	1	1356	23	2.72	<5	2	212	<5	0.04	<10	<10	29	<10	261	2
122421	6.7	1.91	98	123	<0.5	<5	4.07	5	16	18	421	5.22	<1	0.31	<10	0.99	1815	63	0.02	1	1556	33	1.42	<5	4	98	<5	0.08	<10	<10	59	<10	275	3
122422	2.2	2.44	47	72	<0.5	<5	3.22	3	19	13	167	6.17	<1	0.22	10	1.47	1584	90	0.03	1	1709	36	0.84	<5	5	79	<5	0.13	<10	<10	81	<10	273	3
122423	1.7	2.54	30	92	<0.5	<5	3.02	2	18	21	117	5.90	<1	0.25	10	1.62	1459	50	0.04	1	1633	38	0.69	<5	6	89	<5	0.15	<10	<10	88	<10	262	4
122424	1.8	2.53	14	72	<0.5	<5	2.92	2	19	14	186	5.81	<1	0.19	<10	1.62	1423	38	0.03	1	1627	36	0.41	<5	6	75	<5	0.21	<10	<10	87	<10	249	4
122425	<0.2	0.13	<5	11	<0.5	10	>15.00	<1	1	7	7	0.20	<1	0.03	<10	1.77	79	2	0.01	<1	113	<2	0.05	<5	<1	4975	<5	<0.01	<10	<10	4	<10	12	<1
122426	2.1	2.44	27	67	<0.5	<5	4.95	3	18	14	224	5.66	<1	0.19	10	1.51	1883	16	0.03	1	1638	28	0.51	<5	6	168	<5	0.13	<10	<10	81	<10	256	4
122427	2.9	1.82	69	92	<0.5	5	4.53	3	14	19	240	4.37	<1	0.30	<10	1.02	1462	33	0.02	1	1409	32	0.79	<5	3	211	<5	<0.01	<10	<10	47	<10	182	2
122428	3.4	1.85	104	83	<0.5	<5	6.06	5	18	10	374	5.08	<1	0.22	<10	0.99	1830	28	0.02	1	1530	22	1.37	<5	4	157	<5	0.07	<10	<10	63	<10	221	3
122429	2.3	2.41	19	93	<0.5	<5	3.67	2	17	16	267	5.93	<1	0.28	12	1.32	1518	35	0.03	1	1583	32	0.60	<5	5	106	<5	0.06	<10	<10	74	<10	255	3
122430	2.0	2.34	21	84	<0.5	<5	4.08	3	19	11	273	5.79	<1	0.23	13	1.31	1787	40	0.02	1	1642	28	0.53	<5	6	102	<5	0.05	<10	<10	76	<10	280	3
122431	1.9	2.30	12	88	<0.5	<5	2.60	2	20	22	271	5.83	1	0.18	10	1.33	1658	63	0.04	1	1809	31	0.64	<5	7	78	<5	0.17	<10	<10	112	<10	241	4
122432	2.7	2.03	91	78	<0.5	<5	4.27	4	21	7	267	5.92	<1	0.27	<10	1.02	1643	17	0.02	1	1721	31	1.72	<5	5	106	<5	0.08	<10	<10	74	<10	210	4
122433	1.8	2.53	73	121	<0.5	5	3.77	4	19	14	209	6.00	2	0.37	10	1.34	1613	45	0.03	1	1578	53	0.68	<5	7	122	<5	0.05	<10	<10	91	<10	349	3
122434	3.4	2.58	252	92	<0.5	8	3.82	9	18	25	276	6.16	<1	0.28	<10	1.58	1777	44	0.03	2	1523	139	0.60	<5	5	142	<5	0.01	<10	<10	84	<10	321	2
122435	3.7	2.16	91	125	<0.5	6	4.58	5	16	19	314	5.28	1	0.34	<10	1.20	2011	48	0.02	1	1440	53	1.06	<5	4	131	<5	<0.01	<10	<10	74	<10	269	2
122436	1.5	2.19	63	88	<0.5	<5	4.96	3	18	30	113	6.02	1	0.25	<10	1.14	2000	67	0.02	2	1562	24	1.25	<5	5	148	<5	0.06	<10	<10	93	<10	219	5
122437	1.2	2.47	30	99	<0.5	<5	3.04	2	19	14	88	5.74	1	0.26	<10	1.36	1573	35	0.03	2	1674	26	0.37	<5	6	101	<5	0.11	<10	<10	93	<10	244	4
122438	1.6	2.46	29	101	<0.5	<5	3.64	3	19	30	175	5.90	1	0.32	<10	1.28	1556	18	0.03	2	1722	26	0.76	<5	5	135	<5	0.09	<10	<10	78	<10	239	4
122439	2.6	1.94	114	112	<0.5	6	3.62	5	17	11	120	5.69	<1	0.37	<10	1.10	1756	12	0.02	2	1654	29	1.27	<5	5	177	<5	0.01	<10	<10	64	<10	236	2
122440	2.3	2.23	66	108	<0.5	7	4.50	4	17	22	164	5.81	1	0.31	<10	1.17	2009	28	0.02	2	1650	53	0.96	<5	4	144	<5	0.01	<10	<10	72	<10	270	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3672RJ**

Date : Nov-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment34-B

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122441	2.2	2.34	51	92	<0.5	6	4.29	3	18	11	176	5.76	<1	0.38	<10	1.22	1816	11	0.02	2	1691	31	1.00	<5	3	182	<5	<0.01	<10	<10	57	<10	206	2
122442	2.0	2.26	43	102	<0.5	6	3.98	2	18	16	118	5.86	<1	0.32	<10	1.22	1888	9	0.02	2	1757	26	1.11	<5	3	197	<5	0.01	<10	<10	60	<10	158	2
122443	1.5	2.47	44	78	<0.5	6	4.77	3	17	12	79	5.90	<1	0.29	<10	1.44	2397	7	0.02	2	1794	29	0.77	<5	3	182	<5	0.01	<10	<10	60	<10	202	2
122444	3.3	2.15	55	77	<0.5	<5	3.68	3	19	22	205	5.74	<1	0.27	<10	1.23	1763	25	0.02	2	1684	31	1.36	<5	5	91	<5	0.08	<10	<10	63	<10	215	4
122445	1.8	2.28	54	77	<0.5	<5	3.58	4	19	17	101	5.49	<1	0.28	<10	1.23	1466	78	0.04	2	1699	30	0.83	<5	5	98	<5	0.17	<10	<10	73	<10	258	4
122446	0.9	2.19	52	59	<0.5	<5	3.58	3	20	27	24	5.46	<1	0.22	<10	1.25	1593	36	0.03	2	1704	28	0.88	<5	5	103	<5	0.16	<10	<10	67	<10	215	4
122447	5.6	2.13	136	89	<0.5	<5	3.75	6	20	21	214	5.94	<1	0.33	<10	1.20	2820	59	0.02	2	1603	60	1.90	<5	4	58	<5	0.12	<10	<10	66	<10	250	3
122448	3.8	2.01	103	68	<0.5	<5	4.77	5	20	23	177	5.56	<1	0.23	<10	1.16	3095	18	0.02	2	1588	26	1.60	<5	5	85	<5	0.14	<10	<10	66	<10	244	4
122449	2.3	2.18	58	74	<0.5	<5	3.57	3	19	15	108	5.36	<1	0.28	<10	1.13	1988	25	0.03	2	1687	71	1.05	<5	5	95	<5	0.19	<10	<10	73	<10	232	5
122450	<0.2	0.09	<5	11	<0.5	11	>15.00	<1	1	7	7	0.16	<1	0.03	<10	1.48	100	<2	0.01	<1	106	<2	0.06	<5	<1	5471	<5	<0.01	<10	<10	3	<10	8	<1
122501	2.4	2.26	37	65	<0.5	<5	3.34	3	19	20	163	5.41	<1	0.22	<10	1.10	1768	23	0.04	3	1653	30	0.73	<5	5	136	<5	0.20	<10	<10	71	<10	228	5
122502	3.9	2.24	38	61	<0.5	<5	4.17	3	20	24	239	5.49	<1	0.21	<10	1.22	1857	30	0.03	2	1705	21	0.85	<5	5	197	<5	0.18	<10	<10	73	<10	221	5
122503	5.8	1.99	75	93	<0.5	<5	4.01	4	19	14	247	5.32	<1	0.24	<10	1.03	1914	50	0.02	2	1635	98	1.33	<5	5	122	<5	0.14	<10	<10	67	<10	260	5
122504	4.4	2.50	28	132	<0.5	<5	3.91	3	21	22	284	6.10	<1	0.24	<10	1.42	1766	44	0.02	2	1782	26	0.71	<5	5	124	<5	0.12	<10	<10	70	<10	237	4
122505	4.7	0.97	41	95	<0.5	6	4.42	3	16	10	171	4.82	1	0.49	<10	1.00	2193	42	0.01	2	1506	19	0.97	<5	6	341	<5	<0.01	<10	<10	19	<10	175	2
122506	3.9	1.70	56	86	0.5	5	4.15	4	16	17	167	4.68	1	0.44	<10	1.05	1966	50	0.01	3	1371	42	0.87	<5	4	196	<5	<0.01	<10	<10	32	<10	219	2
122507	3.9	0.97	86	93	<0.5	7	9.58	5	12	10	137	3.80	1	0.34	<10	1.01	2713	49	0.01	2	1064	17	0.67	<5	4	419	<5	<0.01	<10	<10	17	<10	214	2
122508	2.6	2.31	47	115	<0.5	5	4.81	3	21	16	168	5.30	1	0.42	<10	1.26	1874	20	0.01	4	1498	25	0.99	<5	5	207	<5	0.03	<10	<10	73	<10	174	4
122509	2.9	2.24	53	96	<0.5	<5	4.23	3	23	9	134	5.45	1	0.23	<10	1.40	2025	16	0.02	2	1523	33	0.80	<5	6	121	<5	0.10	<10	<10	104	<10	230	4
122510	2.3	2.54	22	149	<0.5	<5	3.91	2	24	36	137	5.41	<1	0.28	19	1.66	1770	12	0.04	9	2026	23	0.42	<5	8	123	<5	0.26	<10	<10	110	<10	184	12
122511	3.9	2.38	29	167	<0.5	<5	3.89	3	22	11	228	5.72	1	0.19	<10	1.54	1772	118	0.03	3	1534	25	0.83	<5	7	106	<5	0.15	<10	<10	123	<10	242	5
122512	0.8	2.40	6	542	<0.5	<5	3.56	1	25	54	44	5.39	<1	0.09	30	1.95	1293	6	0.04	16	2575	18	0.16	<5	6	123	<5	0.19	<10	<10	92	<10	164	10
122513	8.8	1.86	110	104	<0.5	<5	4.44	5	22	17	196	5.11	1	0.22	<10	1.23	3668	24	0.01	3	1415	164	1.83	<5	4	109	<5	0.03	<10	<10	75	<10	287	3
122514	11.4	2.07	64	126	<0.5	6	3.50	4	17	12	196	5.34	<1	0.25	<10	1.46	5431	29	0.01	3	1506	84	1.58	<5	4	98	<5	0.01	<10	12	92	<10	343	2
122515	3.4	2.18	84	76	<0.5	<5	3.79	4	21	16	118	5.60	<1	0.21	<10	1.49	3471	21	0.02	3	1451	36	1.54	<5	6	89	<5	0.11	<10	<10	111	<10	182	4
122516	5.5	2.53	58	96	<0.5	<5	4.60	3	23	8	202	5.95	1	0.27	<10	1.63	2889	46	0.02	2	1484	30	1.00	<5	6	121	<5	0.09	<10	<10	109	<10	222	4
122517	2.9	2.53	55	93	<0.5	5	3.92	3	22	18	167	6.11	1	0.21	<10	1.79	2605	98	0.02	2	1551	61	1.00	<5	6	70	<5	0.05	<10	<10	147	<10	246	3
122518	3.6	2.13	73	74	<0.5	<5	5.21	3	22	7	202	5.22	<1	0.24	<10	1.28	2345	22	0.03	2	1451	30	1.11	<5	6	94	<5	0.08	<10	<10	112	<10	215	4
122519	4.2	1.69	427	81	<0.5	<5	2.84	12	23	19	294	5.11	1	0.15	<10	1.18	2003	11	0.03	3	1570	49	1.72	<5	6	60	<5	0.15	<10	<10	129	<10	165	5
122520	2.7	1.67	39	60	<0.5	<5	3.16	2	22	14	214	4.35	<1	0.13	<10	1.23	1805	6	0.03	3	1456	58	1.17	<5	5	72	<5	0.19	<10	<10	105	<10	121	7

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3672RJ**

Date : Nov-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment34-B

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122521	7.5	1.04	140	109	<0.5	<5	4.54	8	15	26	298	4.08	<1	0.22	<10	0.55	2499	25	0.02	3	1212	153	2.57	<5	3	126	<5	0.04	<10	<10	48	11	618	3
122522	5.2	1.42	214	180	<0.5	<5	4.14	9	12	11	287	4.52	<1	0.31	10	0.61	2160	46	0.02	1	1298	105	1.54	<5	3	148	<5	0.02	<10	<10	45	<10	452	2
122523	2.8	1.42	23	80	<0.5	<5	4.98	4	10	21	247	3.83	<1	0.25	12	0.75	2240	45	0.02	2	1280	70	0.44	<5	3	377	<5	0.01	<10	<10	28	<10	466	2
122524	5.4	1.78	15	118	<0.5	<5	3.30	3	12	12	238	4.74	<1	0.28	13	0.85	1718	27	0.03	1	1223	48	0.52	<5	2	121	<5	0.01	<10	<10	41	<10	301	2
122525	<0.2	0.14	<5	16	<0.5	10	>15.00	<1	1	8	13	0.19	<1	0.05	<10	1.37	123	<2	0.01	<1	104	<2	0.06	<5	<1	4912	<5	<0.01	<10	<10	3	<10	19	<1
122526	2.6	1.42	44	97	<0.5	<5	4.32	4	10	11	195	3.99	<1	0.34	11	0.62	1792	21	0.02	1	1217	172	1.01	<5	2	327	<5	0.02	<10	<10	27	<10	337	2
122527	1.5	1.07	17	83	<0.5	<5	4.65	2	7	16	169	3.02	<1	0.29	10	0.46	1353	38	0.02	1	1091	16	0.75	<5	2	424	<5	<0.01	<10	<10	19	<10	127	1
122528	3.7	1.30	26	63	<0.5	<5	3.06	3	11	23	284	3.42	<1	0.29	<10	0.51	1442	80	0.03	1	1024	22	0.70	<5	2	94	<5	0.08	<10	<10	35	<10	220	4
122529	3.3	1.09	19	42	<0.5	<5	7.58	3	9	11	263	2.81	<1	0.21	<10	0.47	2176	43	0.02	<1	975	59	0.48	<5	2	92	<5	0.06	<10	<10	27	<10	281	2
122530	4.8	1.14	381	53	<0.5	<5	3.41	14	11	21	289	3.66	<1	0.22	<10	0.61	1806	38	0.02	1	1077	305	1.56	<5	2	92	<5	0.04	<10	<10	29	<10	531	2
122531	2.4	1.25	13	48	<0.5	<5	3.92	3	11	11	269	3.46	<1	0.20	<10	0.48	1676	40	0.02	1	1091	22	0.40	<5	2	66	<5	0.10	<10	<10	36	<10	290	3
122532	2.3	0.95	38	50	<0.5	<5	3.64	3	9	37	256	2.77	<1	0.24	<10	0.35	1295	30	0.01	1	929	30	0.67	<5	2	52	<5	0.06	<10	<10	23	<10	201	2
122533	3.2	1.38	22	52	<0.5	<5	3.62	2	12	11	317	3.68	<1	0.20	<10	0.64	1656	32	0.02	1	1112	39	0.50	<5	2	65	<5	0.11	<10	<10	39	<10	244	3
122534	5.6	1.39	38	50	<0.5	<5	2.89	3	15	21	425	4.05	<1	0.19	<10	0.67	1933	47	0.02	2	1141	27	0.79	<5	2	45	<5	0.13	<10	<10	43	<10	241	3
122535	3.3	1.52	44	50	<0.5	<5	4.63	2	22	8	233	4.12	<1	0.22	<10	0.81	2399	33	0.01	4	1169	32	0.88	<5	3	57	<5	0.14	<10	<10	58	<10	217	2
122536	2.8	1.44	19	47	<0.5	<5	3.43	2	17	19	407	3.90	<1	0.21	<10	0.74	1793	61	0.02	2	1161	19	0.57	<5	4	50	<5	0.15	<10	<10	67	<10	220	3
122537	5.2	0.40	53	17	<0.5	6	>15.00	3	4	6	296	1.47	<1	0.10	<10	0.20	6356	5	0.01	<1	251	28	0.66	<5	1	199	<5	0.01	<10	<10	13	<10	308	<1
122538	1.7	1.61	21	65	<0.5	<5	3.54	2	17	17	215	4.03	<1	0.25	<10	0.82	1673	20	0.02	2	1343	20	0.61	<5	4	83	<5	0.18	<10	<10	62	<10	199	3
122539	2.6	1.74	33	83	<0.5	<5	3.98	2	15	6	231	4.68	<1	0.29	<10	0.87	2088	25	0.02	1	1224	22	0.97	<5	3	128	<5	0.05	<10	<10	55	<10	252	2
122540	3.0	1.68	17	167	<0.5	<5	3.92	2	20	17	453	4.51	<1	0.28	<10	0.73	1752	104	0.02	2	1189	19	0.70	<5	3	140	<5	0.13	<10	<10	53	<10	225	3
122541	3.1	1.12	35	76	<0.5	<5	3.43	2	10	9	327	2.74	<1	0.32	<10	0.42	1372	38	0.01	1	1060	19	0.36	<5	2	123	<5	0.02	<10	<10	22	<10	178	1
122542	1.9	0.50	49	34	<0.5	6	>15.00	1	6	10	94	1.53	<1	0.16	10	0.19	5400	17	0.01	<1	406	<2	0.42	<5	1	239	<5	0.01	<10	<10	10	<10	59	<1
122543	3.8	0.85	53	49	<0.5	<5	4.88	3	9	15	243	2.67	<1	0.22	<10	0.34	1615	38	0.01	1	855	36	1.06	<5	2	81	<5	0.03	<10	<10	25	<10	171	2
122544	4.0	1.27	83	46	<0.5	<5	5.80	4	17	16	250	4.34	<1	0.20	<10	0.57	2157	38	0.01	3	1013	21	1.76	<5	4	91	<5	0.11	<10	<10	67	<10	229	3
122545	3.8	1.99	99	114	<0.5	6	5.83	5	18	7	211	6.46	<1	0.25	<10	1.03	2837	26	0.01	3	1191	48	2.17	<5	3	116	<5	0.03	<10	12	77	<10	308	3
122546	2.5	1.94	25	68	<0.5	<5	5.01	2	18	12	196	5.37	<1	0.24	<10	0.99	2323	17	0.02	2	1442	22	0.97	<5	4	149	<5	0.08	<10	<10	77	<10	239	3
122547	3.1	2.23	50	64	<0.5	8	4.40	3	20	6	215	6.86	<1	0.31	<10	1.11	2744	29	0.02	3	1568	37	2.11	<5	3	192	<5	0.01	<10	12	70	<10	284	3
122653	6.2	1.77	60	79	<0.5	6	3.20	18	19	8	175	5.71	<1	0.22	<10	1.16	1955	24	0.02	3	1341	47	1.07	<5	4	134	<5	0.01	<10	<10	62	<10	563	2
122654	11.0	1.90	335	136	<0.5	8	4.06	22	21	15	232	5.51	<1	0.38	<10	1.24	2348	43	0.03	3	1397	154	0.92	<5	6	185	<5	<0.01	<10	<10	66	<10	336	2
122655	6.8	0.95	813	156	<0.5	9	4.31	22	15	26	133	3.89	<1	0.55	<10	0.88	2150	32	0.02	2	1178	364	0.87	<5	3	232	<5	<0.01	<10	<10	21	<10	131	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3672RJ**

Date : Nov-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment34-B

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122656	1.2	1.82	84	143	<0.5	6	3.61	3	20	13	16	4.73	<1	0.39	<10	1.17	2028	50	0.03	2	1489	35	0.60	<5	3	130	<5	<0.01	<10	<10	51	<10	106	2
122657	7.0	0.99	500	125	<0.5	5	2.69	17	13	25	32	4.21	<1	0.40	<10	0.38	1100	2	0.01	3	1098	145	3.03	<5	2	122	<5	<0.01	<10	<10	18	<10	493	2
122658	6.2	1.12	176	158	<0.5	<5	2.50	7	12	26	21	3.38	<1	0.43	<10	0.41	1083	11	0.01	2	1131	183	1.93	<5	2	110	<5	<0.01	<10	<10	19	<10	291	2
122659	2.2	1.47	133	162	<0.5	5	2.31	4	13	17	19	4.04	<1	0.39	<10	0.65	1274	<2	0.01	3	1233	31	1.63	<5	2	85	<5	<0.01	<10	<10	29	<10	68	2
122660	2.7	1.12	177	132	<0.5	5	2.23	5	12	27	17	3.86	<1	0.44	<10	0.42	1116	2	0.01	3	1135	37	2.47	<5	2	81	<5	<0.01	<10	<10	22	<10	57	2
122661	2.9	1.00	162	139	<0.5	<5	4.85	6	10	23	17	3.49	<1	0.35	<10	0.46	1534	<2	0.01	2	981	61	2.22	<5	2	129	<5	<0.01	<10	<10	21	<10	254	2
122662	2.6	1.02	146	152	<0.5	<5	0.88	5	14	39	11	3.58	<1	0.43	<10	0.32	593	2	0.01	3	1118	32	2.38	<5	2	44	<5	<0.01	<10	<10	21	<10	61	2
122663	3.8	1.03	479	135	<0.5	<5	0.91	13	14	24	37	3.93	<1	0.39	<10	0.40	663	2	0.01	3	1090	65	2.45	<5	2	53	<5	<0.01	<10	<10	22	<10	107	2
122664	2.9	1.68	664	175	<0.5	5	2.17	18	24	24	76	4.78	<1	0.48	<10	0.70	1376	<2	0.01	5	1190	72	1.77	<5	3	94	<5	<0.01	<10	<10	51	<10	131	2
122665	2.2	1.85	499	223	<0.5	<5	1.77	14	25	10	83	4.73	<1	0.43	<10	0.80	1606	9	0.01	3	1388	52	0.77	<5	4	74	<5	0.07	<10	<10	56	<10	96	2
122666	1.7	1.82	351	291	<0.5	<5	2.06	10	23	13	70	4.31	<1	0.53	<10	0.68	1556	5	0.01	3	1435	38	0.69	<5	4	73	<5	0.09	<10	<10	58	<10	98	3
122667	2.4	2.63	71	186	<0.5	<5	3.15	5	29	9	206	5.99	<1	0.42	<10	1.31	3373	18	0.01	5	1730	46	0.40	<5	4	79	<5	0.08	<10	13	79	<10	245	2
122668	4.2	1.60	409	115	<0.5	6	4.77	14	27	16	216	5.99	<1	0.45	<10	0.76	1530	38	0.01	4	1126	175	4.01	<5	3	124	<5	0.02	<10	<10	39	<10	314	3
122669	6.1	1.36	484	100	<0.5	6	5.32	13	21	14	281	6.34	<1	0.35	<10	0.65	1522	48	0.01	4	1211	62	4.61	<5	3	161	<5	0.01	<10	<10	38	<10	130	3
122670	5.5	1.37	470	122	<0.5	7	3.82	13	26	16	149	5.66	<1	0.40	<10	0.56	1407	15	0.01	4	1313	110	3.97	<5	3	97	<5	0.01	<10	<10	37	<10	83	3
122671	1.9	1.74	310	140	<0.5	6	5.08	9	23	13	102	5.19	<1	0.49	<10	0.76	1384	2	0.01	3	1285	103	2.35	<5	4	127	<5	0.01	<10	<10	48	<10	134	2
122672	2.9	1.79	209	134	<0.5	6	5.64	7	24	14	77	4.61	1	0.44	<10	0.80	1887	5	0.01	3	1508	127	1.58	<5	3	130	<5	0.01	<10	<10	47	<10	124	2
122673	2.7	1.72	290	124	<0.5	6	5.17	8	22	11	97	5.12	<1	0.40	<10	0.79	1599	3	0.01	3	1505	51	2.19	<5	4	112	<5	<0.01	<10	<10	46	<10	86	2
122674	1.8	2.07	124	133	<0.5	6	6.22	4	21	14	69	4.91	<1	0.44	<10	0.94	2006	<2	0.01	2	1458	47	1.29	<5	4	143	<5	<0.01	<10	<10	57	<10	111	2
122675	3.4	2.29	197	121	<0.5	6	5.51	6	22	14	119	6.12	<1	0.38	<10	1.12	2256	26	0.01	2	1517	128	1.84	<5	4	123	<5	0.01	<10	<10	57	<10	95	3
122676	1.5	2.80	131	136	<0.5	7	5.64	4	23	8	76	6.09	1	0.45	<10	1.25	2359	2	0.01	4	1470	47	1.00	<5	4	129	<5	0.01	<10	10	65	<10	97	2
122677	2.7	2.54	137	170	<0.5	7	5.31	5	21	12	123	5.80	<1	0.37	<10	1.22	2219	8	0.01	3	1404	126	1.04	<5	4	139	<5	0.01	<10	12	66	<10	175	2
122678	1.2	2.79	75	152	<0.5	7	5.82	3	23	5	66	5.57	<1	0.50	<10	1.21	2186	<2	0.01	4	1509	48	0.44	<5	5	147	<5	0.01	<10	<10	65	<10	92	2
122679	2.6	2.53	87	146	<0.5	7	5.43	3	23	6	135	6.06	<1	0.44	<10	0.96	2026	6	0.01	3	1546	82	1.20	<5	4	134	<5	<0.01	<10	11	62	<10	102	2
122680	5.3	2.27	93	145	<0.5	6	7.04	4	20	6	319	5.28	<1	0.46	<10	0.82	2606	25	0.01	2	1557	49	0.93	<5	4	220	<5	<0.01	<10	<10	62	<10	144	2
122681	3.0	2.27	154	173	<0.5	7	6.08	5	20	9	154	5.20	<1	0.53	<10	0.86	2077	18	0.01	3	1591	87	1.10	<5	5	146	<5	<0.01	<10	<10	58	<10	127	2
122682	3.5	1.93	63	146	<0.5	6	5.49	7	19	8	221	4.31	<1	0.46	<10	0.81	1962	57	0.01	2	1495	50	0.84	<5	4	141	<5	<0.01	<10	<10	48	10	520	2
122683	2.7	2.29	71	147	<0.5	7	6.08	4	20	8	182	5.34	<1	0.46	<10	1.15	2015	26	0.01	2	1559	78	0.75	<5	4	178	<5	<0.01	<10	<10	52	<10	215	2
122684	2.0	3.07	33	145	<0.5	8	4.72	4	23	5	109	6.23	<1	0.46	<10	1.60	1622	3	0.01	2	1619	213	0.55	<5	5	113	<5	0.01	<10	<10	68	<10	354	3
122685	1.3	3.07	66	142	<0.5	6	4.21	3	24	7	55	6.27	<1	0.42	<10	1.83	1788	2	0.01	3	1595	66	0.85	<5	5	94	<5	0.01	<10	<10	75	<10	114	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3672RJ**

Date : Nov-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment34-B

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122686	1.3	2.73	35	163	<0.5	7	4.27	6	22	4	48	5.58	<1	0.46	<10	1.50	1680	<2	0.02	2	1580	142	0.71	<5	4	103	<5	0.01	<10	<10	71	<10	464	3
122687	2.2	2.25	255	172	<0.5	6	4.94	8	21	9	57	5.22	<1	0.49	<10	0.95	1769	<2	0.01	3	1389	234	1.13	<5	4	149	<5	0.01	<10	<10	62	<10	119	2
122688	1.2	3.03	78	158	<0.5	7	5.05	4	27	5	141	6.81	<1	0.47	<10	1.46	1599	9	0.01	3	1445	57	0.90	<5	5	150	<5	0.01	<10	10	75	<10	155	3
122689	1.1	2.67	52	195	<0.5	5	5.69	4	22	6	60	5.63	<1	0.54	<10	1.25	2147	<2	0.02	3	1630	29	0.74	<5	4	141	<5	0.03	<10	<10	63	<10	159	2
122690	1.6	2.86	76	166	<0.5	6	6.24	3	21	7	62	5.69	<1	0.45	<10	1.74	2239	<2	0.02	3	1305	44	0.75	<5	5	135	<5	0.02	<10	<10	72	<10	75	2
122691	1.9	1.96	454	187	<0.5	<5	3.98	13	22	13	51	5.67	<1	0.50	<10	0.92	1285	<2	0.02	3	1442	49	2.59	<5	4	111	<5	0.04	<10	<10	54	<10	72	3
122692	2.5	1.52	68	232	<0.5	<5	2.14	2	18	14	31	4.80	<1	0.38	10	0.57	1340	3	0.03	3	1241	20	2.26	<5	3	83	<5	0.06	<10	<10	41	<10	47	4
122693	16.3	1.79	67	229	<0.5	<5	3.32	3	25	19	49	5.69	<1	0.34	10	0.69	2139	<2	0.02	5	1024	33	2.31	<5	4	101	<5	0.06	<10	<10	38	<10	184	3
122694	7.5	2.18	64	260	<0.5	6	1.51	3	25	15	40	6.14	<1	0.40	14	0.80	1934	<2	0.03	6	1305	32	1.89	<5	4	45	<5	0.03	<10	<10	46	<10	153	3
122695	6.2	1.22	110	256	<0.5	6	1.35	4	17	48	34	5.05	<1	0.34	11	0.41	1175	<2	0.02	6	1073	33	2.77	<5	2	50	<5	0.01	<10	<10	23	<10	102	3
122696	3.7	2.11	66	207	<0.5	7	1.58	2	20	13	32	5.48	<1	0.29	15	0.91	2008	2	0.03	5	1330	28	1.24	<5	4	51	<5	0.01	<10	<10	40	<10	104	3
122697	3.8	2.19	37	217	<0.5	6	1.85	2	19	34	44	5.48	<1	0.32	14	0.96	2189	<2	0.03	6	1285	25	1.14	<5	3	56	<5	0.01	<10	<10	41	<10	113	3
122698	5.2	1.92	86	192	<0.5	6	0.92	3	21	11	45	5.67	1	0.35	15	0.75	1528	<2	0.02	6	951	33	2.27	<5	3	36	<5	0.01	<10	<10	32	<10	102	3
122699	5.6	2.19	34	221	<0.5	6	0.60	2	21	21	62	5.48	1	0.32	18	0.92	1723	<2	0.02	6	1105	29	1.25	<5	3	22	<5	0.01	<10	<10	39	<10	132	3
122700	2.2	2.20	61	243	<0.5	6	2.24	2	19	10	39	5.29	<1	0.37	18	0.89	2128	<2	0.03	5	1389	21	1.39	<5	4	71	<5	0.01	<10	<10	40	<10	93	3
122701	1.2	2.74	17	221	<0.5	5	1.82	1	20	10	34	5.83	<1	0.30	16	1.16	2326	<2	0.02	5	1336	20	0.30	<5	4	56	<5	0.03	<10	<10	45	<10	104	3
122702	2.0	1.90	94	178	<0.5	<5	1.33	3	22	12	24	5.52	<1	0.35	17	0.83	1600	<2	0.03	5	1571	22	2.42	<5	3	51	<5	0.06	<10	<10	39	<10	95	3
122703	3.5	2.15	37	211	<0.5	<5	1.61	2	21	24	37	5.50	<1	0.30	11	1.03	2184	<2	0.03	5	1399	25	1.55	<5	4	52	<5	0.05	<10	<10	45	<10	127	3
122704	1.6	2.40	5	224	<0.5	<5	2.93	1	20	7	38	5.27	<1	0.32	13	1.10	2377	<2	0.03	5	1563	19	0.49	<5	4	84	<5	0.07	<10	<10	50	<10	95	3
122705	1.9	2.33	18	236	<0.5	<5	2.61	1	27	11	39	5.20	<1	0.33	<10	1.02	2535	<2	0.03	5	1237	19	0.43	<5	4	78	<5	0.04	<10	<10	39	<10	95	2
122706	1.7	2.08	75	306	<0.5	<5	1.66	3	19	8	39	4.36	<1	0.39	<10	0.89	2199	<2	0.03	4	1013	21	0.53	<5	3	66	<5	0.01	<10	<10	29	<10	82	2
122707	2.9	1.98	132	285	<0.5	6	2.11	4	17	12	46	4.52	<1	0.36	11	0.92	2114	<2	0.03	4	1178	20	0.94	<5	3	91	<5	<0.01	<10	<10	30	<10	100	2
122708	2.5	2.00	187	240	<0.5	5	2.64	6	19	8	80	4.99	<1	0.33	<10	0.94	2273	<2	0.03	4	1269	18	1.28	<5	4	116	<5	0.01	<10	<10	35	<10	94	2
122709	4.3	1.86	92	200	<0.5	<5	1.98	8	17	10	186	4.26	<1	0.50	<10	0.69	1576	38	0.01	2	1412	30	0.73	<5	2	65	<5	0.01	<10	<10	36	<10	395	2
122710	2.4	3.02	84	107	<0.5	6	2.28	3	25	6	106	7.04	1	0.22	<10	2.18	3130	<2	0.02	4	1402	34	0.89	<5	7	87	<5	0.01	<10	10	162	<10	115	2
122711	4.8	2.99	90	77	<0.5	7	2.32	4	25	6	132	7.06	<1	0.14	<10	2.27	3224	<2	0.01	4	1391	86	0.91	<5	8	97	<5	0.02	<10	<10	170	<10	136	2
122712	3.0	2.87	90	134	<0.5	6	2.35	4	24	6	145	6.65	1	0.24	<10	2.00	2988	<2	0.02	4	1342	61	0.90	<5	7	79	<5	0.02	<10	<10	164	<10	119	2
122713	5.2	2.63	103	77	<0.5	5	2.22	4	25	8	76	6.21	1	0.20	<10	1.83	2645	<2	0.01	4	1350	52	0.86	<5	5	78	<5	0.01	<10	<10	135	<10	156	2
122714	2.2	2.73	81	113	<0.5	6	3.08	3	25	5	81	6.37	1	0.25	<10	1.87	2964	<2	0.02	4	1374	33	1.00	<5	7	139	<5	0.01	<10	<10	147	<10	96	2
122715	5.1	2.71	43	106	<0.5	6	3.34	2	25	8	186	6.45	<1	0.24	<10	1.94	3227	<2	0.02	4	1333	35	0.95	<5	7	121	<5	0.01	<10	10	157	<10	93	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3672RJ**

Date : Nov-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment34-B

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122716	3.2	2.87	61	104	<0.5	8	3.08	4	27	5	184	6.98	<1	0.25	<10	1.93	2995	<2	0.02	4	1390	87	1.15	<5	7	183	<5	0.01	<10	10	156	<10	280	2
122717	2.1	2.86	46	103	<0.5	7	3.79	2	27	7	99	6.77	1	0.26	<10	1.97	3059	<2	0.02	4	1418	35	0.81	<5	7	189	<5	0.02	<10	10	148	<10	100	2
122718	3.0	2.63	93	119	<0.5	6	4.49	3	24	6	104	6.20	1	0.28	<10	1.77	3423	<2	0.02	4	1308	120	1.03	<5	7	192	<5	0.03	<10	10	132	<10	98	2
122719	2.1	2.86	87	106	<0.5	<5	3.69	6	29	8	80	6.67	<1	0.24	<10	2.12	3019	<2	0.03	5	1400	147	1.31	<5	9	141	<5	0.13	<10	<10	169	<10	449	3
122720	1.2	2.41	56	132	<0.5	<5	4.06	2	26	4	89	5.61	<1	0.28	<10	1.80	2402	<2	0.02	3	1326	36	0.96	<5	8	185	<5	0.15	<10	10	137	<10	108	3
122721	1.8	2.31	49	107	<0.5	<5	4.06	4	25	5	148	5.72	<1	0.27	<10	1.72	2313	<2	0.02	3	1365	41	1.25	<5	7	156	<5	0.12	<10	10	120	<10	153	3
122722	1.5	2.45	76	110	<0.5	<5	4.09	3	25	4	87	5.78	1	0.28	<10	1.95	2454	<2	0.03	4	1367	49	0.99	<5	8	206	<5	0.06	<10	14	137	<10	123	3
122723	3.0	2.40	55	108	<0.5	<5	4.00	3	25	5	107	5.72	<1	0.25	<10	1.82	2811	<2	0.03	4	1350	90	0.82	<5	8	189	<5	0.09	<10	12	147	<10	123	3
122724	1.3	2.52	31	88	<0.5	<5	3.78	2	27	4	110	5.70	1	0.24	<10	1.94	2360	<2	0.03	4	1353	38	0.59	<5	9	150	<5	0.17	<10	<10	148	<10	123	4
122725	1.1	2.48	33	98	<0.5	<5	4.09	2	26	4	118	5.76	1	0.24	<10	2.02	2248	<2	0.03	4	1401	41	0.63	<5	8	206	<5	0.08	<10	11	136	<10	118	3
122726	1.6	2.34	50	117	<0.5	<5	3.52	4	26	4	118	5.76	<1	0.29	<10	1.91	2323	<2	0.02	4	1380	106	1.15	<5	7	154	<5	0.09	<10	10	125	<10	285	3
122727	1.3	2.36	53	111	<0.5	<5	3.60	3	28	6	86	5.90	<1	0.21	<10	1.95	2717	<2	0.02	4	1397	73	1.10	<5	9	124	<5	0.16	<10	10	148	<10	192	4
122728	1.7	2.42	45	129	<0.5	<5	4.34	5	27	4	111	6.03	<1	0.30	<10	1.94	2775	<2	0.02	3	1361	130	1.34	<5	8	143	<5	0.17	<10	10	143	<10	467	3
122729	1.4	2.60	25	119	<0.5	<5	3.09	2	27	5	90	5.87	<1	0.30	<10	2.29	2537	<2	0.02	4	1419	113	0.94	<5	7	112	<5	0.13	<10	12	141	<10	178	3
122730	1.4	2.55	30	110	<0.5	<5	4.15	2	27	5	132	5.88	<1	0.29	<10	2.08	2612	<2	0.02	4	1417	40	0.91	<5	7	160	<5	0.16	<10	11	138	<10	108	3
122731	1.6	2.54	29	150	<0.5	<5	3.54	2	28	4	163	5.79	1	0.31	<10	2.09	2315	<2	0.03	4	1432	41	0.76	<5	7	158	<5	0.14	<10	13	155	<10	102	3
122732	1.8	2.64	16	118	<0.5	<5	3.38	2	27	6	180	6.12	<1	0.27	<10	2.21	2289	<2	0.02	4	1466	50	0.87	<5	7	131	<5	0.09	<10	11	159	<10	131	3
122733	1.1	2.45	41	131	<0.5	5	3.63	2	26	5	91	5.91	1	0.31	<10	1.97	2315	<2	0.03	4	1435	42	0.93	<5	6	164	<5	0.04	<10	13	136	<10	120	3
122734	3.0	1.68	144	145	<0.5	<5	2.36	5	16	7	177	4.16	<1	0.42	<10	0.86	1445	46	0.01	2	1334	38	0.71	<5	3	76	<5	0.02	<10	<10	50	<10	255	2
122735	1.7	2.20	30	151	<0.5	<5	4.39	2	20	4	141	5.16	<1	0.45	<10	1.22	2010	14	0.02	1	1463	30	0.63	<5	3	105	<5	0.03	<10	<10	65	<10	288	2
122736	1.0	2.11	68	127	<0.5	<5	3.82	3	19	7	78	4.99	<1	0.39	<10	1.15	1757	170	0.02	1	1385	34	0.23	<5	4	90	<5	0.12	<10	<10	67	<10	260	2
122737	1.2	1.94	20	130	<0.5	<5	3.89	2	18	6	116	4.53	<1	0.41	<10	1.03	1654	61	0.02	1	1400	25	0.37	<5	3	91	<5	0.12	<10	<10	56	<10	216	2
122738	1.6	2.10	24	126	<0.5	<5	4.51	2	21	5	202	4.99	<1	0.38	<10	1.21	2023	9	0.02	1	1346	23	0.43	<5	4	99	<5	0.13	<10	<10	68	<10	298	3
122739	1.2	2.06	<5	111	<0.5	<5	4.20	2	20	7	227	4.88	<1	0.38	<10	1.13	1545	34	0.02	1	1420	24	0.28	<5	5	87	<5	0.15	<10	<10	71	<10	347	3
122740	1.7	2.17	26	114	<0.5	<5	5.14	2	22	4	185	5.29	<1	0.41	<10	1.11	1878	27	0.02	1	1454	31	0.62	<5	5	110	<5	0.14	<10	<10	66	<10	323	3
122741	1.5	1.86	396	144	<0.5	5	6.47	11	21	6	51	5.36	<1	0.37	<10	1.14	1812	<2	0.01	2	1402	30	2.09	<5	4	135	<5	0.02	<10	<10	56	<10	66	2
122742	2.2	2.99	50	174	<0.5	6	4.72	2	26	12	53	6.25	<1	0.46	<10	2.12	2195	<2	0.01	3	1687	54	0.71	<5	6	126	<5	0.02	<10	10	88	<10	94	3
122743	1.8	2.37	76	117	<0.5	6	5.42	3	24	9	48	6.32	<1	0.26	<10	1.53	2055	<2	0.03	2	1768	34	1.10	<5	5	168	<5	0.03	<10	<10	84	<10	106	3
122744	1.2	2.18	69	196	<0.5	<5	4.63	3	25	11	54	6.25	<1	0.42	<10	1.14	1563	<2	0.03	3	1798	29	1.58	<5	5	158	<5	0.06	<10	10	80	<10	66	3
122745	0.9	2.37	47	169	<0.5	<5	4.70	2	23	6	54	6.09	<1	0.35	<10	1.45	1985	<2	0.02	2	1901	31	0.78	<5	4	189	<5	0.05	<10	11	75	<10	91	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3672RJ**

Date : Nov-04-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/Shipment34-B

Sample type: core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122746	1.2	2.41	56	157	<0.5	<5	6.56	3	23	7	49	5.88	<1	0.33	10	1.59	2997	<2	0.02	2	1661	30	0.54	<5	4	202	<5	0.05	<10	11	75	<10	110	2
122747	1.4	2.57	40	121	<0.5	<5	4.30	2	27	5	61	6.65	<1	0.26	<10	1.71	2160	<2	0.02	3	1812	28	0.72	<5	5	148	<5	0.08	<10	12	96	<10	95	3
122748	0.6	2.63	27	177	<0.5	<5	4.33	2	27	6	51	6.53	<1	0.38	<10	1.61	1796	<2	0.03	2	1825	29	0.82	<5	5	142	<5	0.12	<10	<10	92	<10	111	3
122749	0.6	2.36	34	146	<0.5	5	5.25	3	26	4	52	6.17	<1	0.31	<10	1.35	1666	<2	0.02	2	1795	25	0.58	<5	4	158	<5	0.04	<10	11	77	<10	110	3
122750	0.4	2.49	29	187	<0.5	<5	5.88	2	25	6	42	6.12	<1	0.41	<10	1.42	1830	<2	0.02	2	1693	24	0.52	<5	4	184	<5	0.06	<10	12	70	<10	93	3
122751	0.5	2.53	32	154	<0.5	<5	5.52	2	27	6	55	6.47	<1	0.34	<10	1.52	1949	<2	0.01	3	1759	26	0.68	<5	5	154	<5	0.07	<10	13	74	<10	106	3
122752	1.1	2.41	89	186	<0.5	7	6.84	4	26	8	58	6.58	<1	0.41	<10	1.28	2365	<2	0.01	3	1748	37	1.39	<5	5	181	<5	0.02	<10	10	77	<10	136	3
122753	1.8	1.27	391	132	<0.5	6	4.56	10	29	7	60	5.32	<1	0.34	<10	0.59	1523	2	0.01	3	1758	44	3.42	<5	3	109	<5	0.01	<10	<10	37	<10	53	2
122754	1.6	1.98	325	154	<0.5	7	4.57	9	19	11	41	5.55	<1	0.41	<10	1.13	1793	<2	0.01	1	1539	54	1.85	<5	2	135	<5	<0.01	<10	<10	46	<10	81	2
122755	1.5	1.98	214	147	<0.5	6	4.01	6	19	7	32	5.09	<1	0.38	<10	1.22	1756	<2	0.01	1	1512	37	1.05	<5	2	135	<5	0.01	<10	<10	46	<10	56	2
122756	2.3	1.78	321	122	<0.5	6	5.94	10	18	17	37	5.01	<1	0.33	<10	1.05	2107	<2	0.01	1	1491	67	1.58	<5	2	173	<5	<0.01	<10	<10	42	<10	219	2
122757	0.8	2.31	70	175	<0.5	6	4.10	3	19	8	24	5.59	<1	0.45	<10	1.49	1956	<2	0.01	1	1687	36	0.99	<5	3	139	<5	0.01	<10	<10	57	<10	53	3
122758	1.1	2.21	66	133	<0.5	7	4.65	3	20	10	39	5.73	<1	0.35	<10	1.40	2105	<2	0.01	1	1652	28	1.07	<5	2	156	<5	0.01	<10	<10	62	<10	54	2
122759	1.1	2.09	53	170	<0.5	7	2.68	2	19	6	41	5.56	<1	0.41	<10	1.51	1647	<2	0.01	1	1659	30	1.04	<5	2	85	<5	<0.01	<10	<10	55	<10	45	2
122760	1.1	1.34	98	233	<0.5	6	5.99	4	18	9	41	5.08	<1	0.38	<10	1.21	2165	<2	0.01	1	1684	32	0.87	<5	2	167	<5	<0.01	<10	<10	39	<10	109	2
122761	0.9	0.92	257	407	0.5	7	4.32	7	19	4	26	5.62	<1	0.39	<10	0.95	1975	<2	0.01	1	1529	25	1.02	<5	3	153	<5	<0.01	<10	<10	28	<10	66	2
122762	1.8	0.63	444	170	<0.5	6	4.96	12	19	10	44	5.41	<1	0.37	<10	0.73	2037	<2	0.01	2	1491	30	2.03	<5	3	175	<5	<0.01	<10	<10	22	<10	54	2
122763	1.9	1.19	35	88	<0.5	<5	4.45	5	15	114	147	2.95	1	0.11	<10	0.77	1048	31	0.02	11	1627	25	0.12	<5	7	87	<5	0.11	<10	<10	88	<10	310	10
122764	2.5	0.81	33	53	<0.5	<5	2.40	3	13	97	191	2.13	1	0.10	<10	0.66	658	36	0.02	10	1803	18	0.10	<5	4	57	<5	0.13	<10	<10	64	<10	184	11
122765	3.9	0.70	37	60	<0.5	<5	1.98	4	21	102	423	1.59	<1	0.10	<10	0.52	389	77	0.02	19	1820	19	0.11	<5	3	69	<5	0.15	<10	<10	57	<10	219	10
122766	2.4	1.07	34	37	<0.5	<5	4.67	3	21	116	322	2.81	<1	0.07	<10	1.10	1327	109	0.03	19	1651	20	0.14	<5	4	96	<5	0.11	<10	<10	57	<10	224	8
122767	2.7	0.84	24	76	<0.5	<5	3.03	4	17	103	432	2.16	1	0.10	<10	0.92	788	93	0.03	18	1632	104	0.23	<5	3	73	<5	0.13	<10	<10	59	<10	379	7
122768	1.3	1.01	36	43	<0.5	<5	6.44	3	20	136	183	2.86	1	0.07	<10	1.08	1356	73	0.03	20	1485	20	0.31	<5	5	114	<5	0.12	<10	<10	76	<10	157	5
122769	1.4	1.49	21	63	<0.5	<5	3.67	2	24	157	205	3.97	<1	0.08	<10	1.63	1226	60	0.03	26	1784	22	0.29	<5	5	87	<5	0.16	<10	<10	103	<10	184	5

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3699-RA1

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 35**
Attn: **Sue Deane**

Nov-05-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122548	0.20	0.23	7.3
122549	0.11		3.7
122550	0.01		<0.1
122551	0.14		3.0
122301	0.02		0.9
122302	0.15		1.8
122303	0.02		0.7
122304	0.01		0.9
122305	0.01		0.4
122306	0.01	<0.01	0.5
122307	0.01		0.3
122308	0.01		0.5
122309	0.01		0.4
122310	0.01		0.6
122311	0.02		0.5
122312	0.02		0.7
122313	0.03		0.7
122314	0.01		0.6
122315	0.05		0.5
122316	0.05	0.04	0.6
122317	0.04		0.5
122318	0.05		0.6
*0211	2.14		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3699-RA2

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 35**
Attn: **Sue Deane**

Nov-05-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122319	0.04	0.05	0.6
122320	0.14		0.8
122321	0.13		0.7
122322	0.02		0.5
122323	0.01		0.5
122324	<0.01		0.4
122325	<0.01		<0.1
122326	0.01		0.5
122327	0.01		0.5
122328	<0.01	<0.01	0.4
122329	0.11		1.2
122330	0.03		0.5
122331	0.03		0.7
122332	0.04		0.7
122333	0.20		2.2
122334	0.22		2.3
122335	0.08		0.7
122336	0.02		0.9
122337	0.01		0.2
122338	0.06	0.06	0.8
122339	0.04		0.9
122340	0.13		1.6
*0211	2.17		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3699-RA3

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 35**
Attn: **Sue Deane**

Nov-05-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122341	0.06	0.07	2.2
122342	0.03		1.3
122343	0.08		2.1
122344	0.02		1.3
122345	0.09		2.0
122346	2.35		6.2
122347	0.08		2.5
122348	0.41		5.3
122349	0.02		1.0
122350	<0.01	<0.01	<0.1
122351	0.03		1.5
122351A	0.01		0.8
122352	0.01		0.9
122352A	0.01		0.8
122353	0.02		0.6
122354	0.02		0.6
122355	<0.01		0.8
122356	0.08		0.9
122357	0.01		0.9
122358	0.01	<0.01	0.8
122359	0.01		0.8
122360	0.01		0.9
*0211	2.15		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3699-RA4

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 35**
Attn: **Sue Deane**

Nov-05-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122361	0.04	0.05	0.4
122362	<0.01		0.2
122363	0.01		0.2
122364	<0.01		0.2
122365	<0.01		0.9
122366	0.01		1.2
122367	0.02		0.5
122368	<0.01		0.4
122369	0.01		0.3
122370	0.03	0.03	0.8
122371	0.01		0.6
122372	0.01		0.7
122373	0.03		0.7
122374	0.01		0.8
122375	<0.01		<0.1
122376	<0.01		1.0
122377	0.11		2.1
122378	0.07		1.9
122379	0.05		1.5
122380	0.01	<0.01	0.8
122381	0.01		1.0
122382	0.27		1.4
*0211	2.21		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3699-RA5

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 35**
Attn: **Sue Deane**

Nov-05-08

We hereby certify the following assay of 22 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122382A	0.04	0.06	1.1
122383	0.05		1.4
122384	0.15		3.1
122385	<0.01		0.7
122386	0.02		1.2
122387	0.02		0.7
122388	0.02		0.7
122389	0.02		0.8
122390	0.01		0.6
122391	0.01	<0.01	0.6
122392	0.17		2.1
122393	0.28		21.1
122394	0.02		2.7
122395	0.06		3.1
122396	0.12		4.7
122397	0.08		3.5
122398	4.23		8.3
122399	1.94		11.7
122400	<0.01		<0.1
122401	2.71	3.10	17.0
122402	5.71		6.4
122403	0.05		2.9
*0211	2.13		
*BLANK	<0.01		

Certified by _____



Assayers Canada
8282 Sherbrooke St.
Vancouver, B.C.
V5X 4R6
Tel: (604) 327-3436
Fax: (604) 327-3423

Quality Assaying for over 25 Years

Assay Certificate

8V-3699-RA6

Company: **Ascot Resources Ltd**
Project: **Dilworth/shipment 35**
Attn: **Sue Deane**

Nov-05-08

We *hereby certify* the following assay of 7 core samples submitted Oct-14-08

Sample Name	Au g/tonne	Au-Check g/tonne	Ag g/tonne
122404	0.05	0.06	3.0
122405	0.03		2.1
122406	0.02		3.3
122407	0.02		4.0
122408	0.21		15.1
122409	0.03		3.1
122410	0.02		4.1
*0211	2.12		
*BLANK	<0.01		

Certified by _____

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3699RJ**

Date : Nov-05-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 35

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122548	7.3	1.70	192	75	<0.5	5	4.67	7	15	23	158	4.41	<1	0.39	<10	0.73	2643	10	0.02	2	1318	176	1.60	<5	3	167	<5	0.01	<10	<10	44	<10	256	2
122549	3.7	1.52	154	65	<0.5	<5	4.79	5	11	25	162	3.70	<1	0.35	<10	0.61	2422	31	0.01	2	1273	33	1.04	<5	3	167	<5	0.02	<10	<10	42	<10	141	2
122550	<0.2	0.08	27	11	<0.5	11	>15.00	1	1	7	6	0.08	<1	0.03	<10	1.38	69	<2	0.01	<1	64	<2	0.04	<5	<1	4925	<5	<0.01	<10	14	2	<10	6	<1
122551	3.0	1.49	67	61	0.7	5	4.39	3	11	22	165	3.83	<1	0.34	<10	0.61	2403	22	0.02	2	1273	32	0.93	<5	4	140	<5	0.01	<10	<10	51	<10	136	2
122301	0.9	1.61	56	227	<0.5	5	3.10	2	13	9	32	4.20	<1	0.35	<10	0.98	1872	<2	0.03	3	1331	15	0.55	<5	3	120	<5	<0.01	<10	<10	29	<10	78	2
122302	1.8	1.17	203	279	<0.5	6	3.98	6	14	16	25	4.46	<1	0.37	<10	0.85	1697	<2	0.02	3	1279	80	1.14	<5	4	163	<5	<0.01	<10	<10	19	<10	130	2
122303	0.7	1.58	46	219	<0.5	6	3.28	2	12	8	20	4.24	<1	0.37	<10	1.05	1670	<2	0.03	3	1279	22	0.64	<5	4	151	<5	<0.01	<10	<10	30	<10	77	2
122304	0.9	1.50	54	211	<0.5	6	2.80	2	15	10	35	4.63	<1	0.35	<10	1.03	1570	<2	0.03	3	1336	27	0.97	<5	4	110	<5	<0.01	<10	<10	26	<10	104	2
122305	0.4	0.61	21	220	<0.5	5	5.69	1	11	10	17	3.36	<1	0.36	<10	0.81	1906	<2	0.04	3	1141	9	0.32	<5	4	403	<5	<0.01	<10	<10	13	<10	56	2
122306	0.5	0.59	20	207	<0.5	6	3.50	2	13	13	26	4.09	<1	0.34	<10	0.94	1620	<2	0.04	3	1265	13	0.40	<5	4	196	<5	<0.01	<10	<10	15	<10	148	2
122307	0.3	0.65	21	180	<0.5	6	4.62	1	12	13	16	4.14	<1	0.29	10	1.05	1799	<2	0.06	3	1177	9	0.25	<5	5	275	<5	<0.01	<10	<10	20	<10	64	2
122308	0.5	1.71	25	189	<0.5	6	2.63	1	14	11	20	4.94	<1	0.34	12	0.99	1490	<2	0.04	3	1399	16	0.43	<5	5	101	<5	<0.01	<10	<10	36	<10	87	3
122309	0.4	0.86	27	160	<0.5	5	3.23	1	12	14	13	4.08	<1	0.30	<10	0.73	1411	<2	0.05	3	1178	9	0.43	<5	4	143	<5	<0.01	<10	<10	24	<10	61	2
122310	0.6	0.89	24	211	<0.5	5	3.16	2	13	9	20	4.05	<1	0.35	10	0.87	1405	<2	0.04	2	1240	9	0.46	<5	4	147	<5	<0.01	<10	<10	19	<10	107	2
122311	0.5	0.85	29	232	<0.5	5	1.99	1	13	13	22	3.92	<1	0.42	<10	0.68	1140	<2	0.02	3	1179	8	1.27	<5	3	75	<5	<0.01	<10	<10	16	<10	50	2
122312	0.7	0.58	24	212	<0.5	<5	3.05	2	14	15	46	3.69	<1	0.38	<10	0.72	1332	<2	0.02	3	1340	12	1.43	<5	4	160	<5	<0.01	<10	<10	12	<10	70	2
122313	0.7	0.52	24	156	<0.5	6	6.63	2	10	34	6	3.82	<1	0.30	<10	0.85	2004	<2	0.02	2	986	19	0.68	<5	4	401	<5	<0.01	<10	<10	10	<10	155	2
122314	0.6	0.81	22	188	<0.5	<5	2.83	2	13	28	31	2.95	<1	0.38	<10	0.48	940	<2	0.02	3	1340	14	0.51	<5	3	127	<5	<0.01	<10	<10	12	<10	159	2
122315	0.5	0.48	22	154	<0.5	8	8.60	1	11	27	8	4.74	<1	0.32	<10	1.53	2578	<2	0.02	2	1157	9	0.50	<5	3	589	<5	<0.01	<10	<10	10	<10	74	2
122316	0.6	1.29	54	169	<0.5	6	4.52	2	12	15	24	4.12	<1	0.32	<10	1.00	1776	<2	0.02	3	1235	12	0.69	<5	4	205	<5	<0.01	<10	<10	25	<10	70	2
122317	0.5	1.51	55	218	<0.5	5	2.55	2	14	12	22	4.19	<1	0.39	<10	1.05	1404	<2	0.02	4	1298	16	0.73	<5	4	121	<5	<0.01	<10	<10	27	<10	76	2
122318	0.6	1.81	75	207	<0.5	5	2.94	3	14	13	19	3.99	<1	0.32	10	1.07	1572	<2	0.03	4	1287	19	0.49	<5	4	166	<5	0.01	<10	<10	40	<10	80	2
122319	0.6	1.79	95	206	<0.5	<5	1.91	3	15	9	27	4.31	<1	0.31	<10	1.11	1413	<2	0.04	3	1381	15	0.72	<5	3	97	<5	0.04	<10	<10	43	<10	90	3
122320	0.8	1.44	171	184	<0.5	<5	2.61	5	14	9	26	4.01	<1	0.28	<10	0.89	1300	<2	0.03	2	1316	41	1.12	<5	3	133	<5	0.03	<10	<10	35	<10	99	3
122321	0.7	1.56	127	200	<0.5	<5	1.99	4	15	8	24	3.80	<1	0.33	<10	0.96	1188	<2	0.03	2	1330	41	0.82	<5	3	81	<5	0.07	<10	<10	35	<10	121	3
122322	0.5	1.33	57	229	<0.5	<5	2.32	2	15	8	29	3.41	<1	0.31	<10	0.77	1138	<2	0.02	2	1283	13	0.92	<5	2	86	<5	0.03	<10	<10	29	<10	73	2
122323	0.5	1.44	54	218	<0.5	<5	2.82	2	14	6	23	3.88	<1	0.38	<10	0.69	1305	<2	0.02	2	1290	14	1.12	<5	2	114	<5	0.04	<10	<10	31	<10	74	2
122324	0.4	1.50	17	197	<0.5	<5	3.64	1	14	7	24	3.79	<1	0.35	<10	0.69	1446	<2	0.02	2	1258	13	0.66	<5	3	170	<5	0.08	<10	<10	32	<10	60	3
122325	<0.2	0.10	<5	24	<0.5	9	>15.00	<1	1	6	2	0.09	1	0.05	<10	2.21	54	<2	0.01	<1	86	<2	0.05	<5	<1	4139	<5	<0.01	<10	<10	2	<10	1	<1
122326	0.5	1.40	61	176	<0.5	<5	2.59	2	16	9	29	3.62	<1	0.29	<10	0.74	1245	<2	0.02	2	1224	15	0.61	<5	2	93	<5	0.07	<10	<10	38	<10	57	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3699RJ**

Date : Nov-05-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 35

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122327	0.5	1.60	56	230	<0.5	<5	2.96	2	14	7	17	4.12	<1	0.36	<10	0.85	1241	<2	0.02	2	1263	18	0.89	<5	2	133	<5	0.09	<10	<10	32	<10	69	3
122328	0.4	1.46	16	229	<0.5	<5	3.85	2	14	14	17	3.89	<1	0.25	<10	0.83	1244	<2	0.03	2	1251	70	0.57	<5	3	183	<5	0.08	<10	<10	41	<10	132	3
122329	1.2	1.52	127	220	<0.5	<5	3.87	5	15	7	26	4.37	<1	0.31	<10	0.77	1421	<2	0.04	2	1256	168	1.25	<5	3	186	<5	0.10	<10	<10	43	<10	297	3
122330	0.5	1.70	24	213	<0.5	<5	3.33	1	17	8	24	4.33	<1	0.31	10	0.86	1407	<2	0.03	2	1283	26	0.53	<5	3	135	<5	0.13	<10	<10	41	<10	85	3
122331	0.7	1.57	47	207	<0.5	<5	2.78	2	15	7	26	4.18	<1	0.33	<10	0.74	1464	<2	0.03	2	1217	16	0.84	<5	3	119	<5	0.09	<10	<10	35	<10	82	3
122332	0.7	1.66	40	180	<0.5	<5	1.27	2	14	10	28	4.48	<1	0.30	10	0.80	1266	<2	0.02	2	1199	19	0.77	<5	3	55	<5	0.02	<10	<10	36	<10	170	2
122333	2.2	1.35	332	156	<0.5	<5	0.83	9	16	7	28	4.60	<1	0.37	10	0.59	928	<2	0.02	3	1131	37	2.23	<5	2	35	<5	0.04	<10	<10	24	<10	131	3
122334	2.3	1.22	273	170	<0.5	<5	1.61	7	15	11	32	3.94	<1	0.32	<10	0.60	1123	<2	0.02	3	1063	35	1.83	<5	2	56	<5	0.06	<10	<10	21	<10	90	3
122335	0.7	1.53	136	222	<0.5	<5	3.52	4	15	6	21	3.78	<1	0.38	11	0.74	1628	<2	0.02	2	1211	21	0.91	<5	3	120	<5	0.10	<10	<10	27	<10	88	3
122336	0.9	1.54	11	187	<0.5	<5	3.31	1	16	7	21	3.68	<1	0.32	10	0.75	1410	<2	0.02	2	1232	11	0.35	<5	3	127	<5	0.10	<10	<10	26	<10	87	3
122337	0.2	1.61	<5	748	<0.5	<5	4.96	1	14	5	18	3.36	<1	0.35	<10	0.80	1540	<2	0.02	2	1185	10	0.10	<5	3	214	<5	0.08	<10	<10	27	<10	87	3
122338	0.8	1.48	108	149	<0.5	<5	2.05	3	15	10	24	4.37	<1	0.27	<10	0.70	1136	<2	0.02	3	946	20	1.38	<5	2	62	<5	0.04	<10	<10	24	<10	110	2
122339	0.9	1.73	67	219	<0.5	<5	0.78	2	15	7	26	4.52	<1	0.33	<10	0.84	987	<2	0.02	2	1159	30	1.20	<5	3	34	<5	0.02	<10	<10	29	<10	105	3
122340	1.6	1.57	250	156	<0.5	<5	0.95	7	17	12	28	4.66	<1	0.30	<10	0.81	994	<2	0.02	4	1162	24	1.84	<5	3	34	<5	0.06	<10	<10	31	<10	64	3
122341	2.2	2.34	203	169	<0.5	5	1.10	6	20	11	36	5.70	2	0.29	<10	1.18	1329	<2	0.02	7	1234	26	1.52	<5	3	39	<5	0.04	<10	<10	43	<10	76	3
122342	1.3	2.06	138	174	<0.5	5	1.36	4	16	14	29	4.80	1	0.27	<10	1.03	1296	<2	0.02	6	1398	18	1.00	<5	3	49	<5	0.02	<10	<10	38	<10	71	3
122343	2.1	1.99	132	206	<0.5	7	0.55	5	18	11	25	4.94	<1	0.32	<10	1.01	1005	<2	0.02	7	1282	38	1.53	<5	3	35	<5	0.01	<10	<10	34	<10	93	3
122344	1.3	2.11	69	201	<0.5	8	2.46	3	21	13	40	5.49	<1	0.30	<10	1.01	1346	<2	0.02	7	1385	23	1.73	<5	3	82	<5	0.01	<10	<10	39	<10	76	3
122345	2.0	1.90	130	193	<0.5	7	0.99	4	18	8	38	4.87	<1	0.31	<10	0.88	1002	<2	0.02	5	1377	31	1.59	<5	3	43	<5	<0.01	<10	<10	31	<10	82	3
122346	6.2	2.33	390	180	<0.5	7	0.75	12	19	13	36	6.23	<1	0.27	<10	1.23	1175	<2	0.02	5	1619	61	2.06	<5	3	37	<5	0.02	<10	<10	41	<10	222	3
122347	2.5	2.32	340	177	<0.5	6	1.25	10	17	11	27	5.41	<1	0.28	<10	1.22	1293	2	0.02	2	1433	44	1.26	<5	3	45	<5	0.01	<10	<10	37	<10	156	2
122348	5.3	2.07	399	150	<0.5	6	1.30	13	17	19	31	5.85	<1	0.24	<10	1.00	1236	<2	0.01	2	1233	121	2.00	<5	3	46	<5	<0.01	<10	<10	34	<10	289	3
122349	1.0	2.88	68	153	<0.5	7	1.06	3	20	9	26	6.08	<1	0.27	10	1.45	1484	<2	0.02	2	1821	25	0.42	<5	4	38	<5	<0.01	<10	<10	49	<10	117	3
122350	<0.2	0.10	<5	14	<0.5	10	>15.00	<1	1	7	1	0.08	<1	0.02	<10	2.54	48	<2	0.01	<1	84	<2	0.03	<5	<1	4551	<5	<0.01	<10	<10	2	<10	4	<1
122351	1.5	2.81	92	152	<0.5	8	1.52	4	22	7	21	6.49	<1	0.29	<10	1.39	1612	<2	0.02	2	1774	35	1.11	<5	4	62	<5	<0.01	<10	<10	45	<10	142	3
122351A	0.8	2.78	33	155	<0.5	7	3.31	2	19	15	22	5.70	<1	0.31	11	1.34	1735	<2	0.02	3	1642	23	0.43	<5	4	97	<5	<0.01	<10	<10	45	<10	99	2
122352	0.9	2.86	48	336	<0.5	7	3.07	2	21	15	20	6.07	<1	0.33	<10	1.50	1713	<2	0.02	3	1579	23	1.03	<5	4	90	<5	<0.01	<10	<10	49	<10	95	3
122352A	0.8	3.13	39	146	<0.5	8	4.08	2	20	13	23	6.07	<1	0.30	<10	1.78	1932	<2	0.01	3	1623	21	0.39	<5	4	108	<5	<0.01	<10	<10	49	<10	101	2
122353	0.6	2.97	25	154	<0.5	7	4.84	2	20	12	22	5.58	<1	0.31	<10	1.63	1984	<2	0.02	3	1622	17	0.37	<5	4	127	<5	<0.01	<10	<10	47	<10	104	2
122354	0.6	2.49	19	135	<0.5	7	5.60	1	16	11	21	5.45	<1	0.30	<10	1.30	1912	<2	0.01	2	1601	20	1.02	<5	4	139	<5	<0.01	<10	<10	40	<10	87	2

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3699RJ**

Date : Nov-05-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 35

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122355	0.8	2.74	57	185	<0.5	7	3.52	2	19	9	19	5.90	<1	0.35	10	1.56	1610	<2	0.01	3	1756	17	0.72	<5	4	127	<5	<0.01	<10	<10	44	<10	100	3
122356	0.9	2.02	98	172	<0.5	7	3.75	3	14	10	23	4.54	<1	0.31	<10	1.17	1354	<2	0.01	2	1739	16	0.89	<5	4	140	<5	<0.01	<10	<10	30	<10	89	2
122357	0.9	2.15	43	164	<0.5	7	2.38	2	17	12	22	4.90	1	0.32	<10	1.28	1175	<2	0.01	3	1486	19	0.95	<5	4	97	<5	<0.01	<10	<10	33	<10	98	2
122358	0.8	1.33	13	168	<0.5	7	3.75	1	13	27	17	4.24	<1	0.27	<10	1.37	1731	<2	0.01	2	1056	18	0.88	<5	3	168	<5	<0.01	<10	<10	23	<10	58	2
122359	0.8	2.62	33	170	<0.5	6	1.13	2	18	12	21	5.60	<1	0.30	<10	1.70	929	<2	0.01	3	1536	22	1.10	<5	4	40	<5	<0.01	<10	<10	37	<10	103	3
122360	0.9	2.76	26	167	<0.5	7	2.35	2	19	15	23	5.66	<1	0.29	<10	1.80	1206	<2	0.01	3	1627	21	0.80	<5	4	89	<5	<0.01	<10	<10	40	<10	95	3
122361	0.4	2.99	132	448	<0.5	7	4.27	4	17	11	20	5.32	1	0.33	10	1.84	1429	<2	0.02	3	1621	31	0.19	<5	4	237	<5	<0.01	<10	<10	44	<10	104	3
122362	0.2	3.32	<5	1164	<0.5	6	3.24	1	19	11	15	5.93	<1	0.30	12	2.14	1300	<2	0.02	3	1796	21	0.05	<5	4	444	<5	0.01	<10	<10	55	<10	113	3
122363	0.2	3.04	13	3106	<0.5	7	3.55	2	17	7	19	5.45	<1	0.34	13	1.90	1330	<2	0.02	3	1618	18	0.09	<5	4	584	<5	<0.01	<10	<10	47	<10	98	3
122364	0.2	2.83	<5	3730	<0.5	7	3.72	1	17	9	22	5.14	1	0.37	12	1.66	1366	<2	0.02	3	1603	18	0.12	<5	4	392	<5	<0.01	<10	<10	44	<10	98	2
122365	0.9	2.78	47	506	<0.5	<5	3.41	2	17	6	19	5.45	<1	0.35	10	1.51	1438	<2	0.03	3	1697	20	0.57	<5	4	190	<5	0.03	<10	<10	46	<10	92	3
122366	1.2	2.53	44	439	<0.5	<5	3.61	2	19	5	22	5.03	<1	0.38	10	1.22	1617	<2	0.02	3	1638	18	0.38	<5	4	187	<5	0.08	<10	<10	37	<10	93	3
122367	0.5	2.84	49	893	<0.5	<5	4.95	2	20	6	21	5.51	<1	0.37	10	1.53	1862	<2	0.03	2	1608	19	0.37	<5	6	300	<5	0.21	<10	<10	61	<10	95	6
122368	0.4	2.78	9	1098	<0.5	<5	5.12	1	22	6	24	5.40	<1	0.32	<10	1.53	1745	<2	0.02	2	1699	19	0.31	<5	5	296	<5	0.20	<10	<10	53	<10	89	4
122369	0.3	2.90	5	280	<0.5	<5	4.45	1	20	6	18	5.59	<1	0.36	10	1.51	1692	<2	0.02	2	1691	20	0.21	<5	4	208	<5	0.17	<10	<10	51	<10	96	4
122370	0.8	2.96	18	268	<0.5	<5	4.43	2	20	7	31	5.83	<1	0.39	10	1.44	2144	<2	0.02	3	1771	24	0.44	<5	4	175	<5	0.12	<10	<10	44	<10	112	3
122371	0.6	2.89	6	196	<0.5	<5	5.00	1	21	7	22	5.60	<1	0.36	10	1.43	2253	<2	0.02	2	1742	20	0.44	<5	4	204	<5	0.10	<10	<10	46	<10	97	3
122372	0.7	3.07	<5	220	<0.5	<5	4.23	1	17	9	23	6.32	<1	0.35	11	1.54	1965	<2	0.02	3	1590	22	0.71	<5	5	165	<5	0.06	<10	<10	44	<10	93	3
122373	0.7	2.67	25	184	<0.5	6	2.40	2	19	7	20	6.22	<1	0.35	<10	1.44	1387	<2	0.02	3	1754	27	1.36	<5	4	103	<5	<0.01	<10	<10	37	<10	128	3
122374	0.8	2.59	25	192	0.5	6	2.34	2	18	8	20	5.55	<1	0.36	<10	1.56	1342	<2	0.02	3	2038	25	0.67	<5	5	112	<5	<0.01	<10	<10	37	<10	127	2
122375	<0.2	0.21	7	40	<0.5	11	>15.00	<1	1	6	2	0.18	<1	0.07	<10	2.34	76	<2	0.01	<1	94	<2	0.03	<5	<1	4511	<5	<0.01	<10	<10	4	<10	5	<1
122376	1.0	0.76	7	100	<0.5	10	>15.00	1	6	22	5	3.21	<1	0.20	10	1.13	5380	<2	0.02	<1	711	<2	0.09	<5	5	1765	<5	<0.01	<10	<10	15	<10	48	<1
122377	2.1	1.79	246	192	<0.5	6	3.24	7	20	29	20	5.10	<1	0.37	<10	0.98	1529	<2	0.02	3	1532	27	1.90	<5	4	196	<5	<0.01	<10	<10	31	<10	87	2
122378	1.9	2.37	129	264	<0.5	7	3.25	6	19	9	33	5.31	<1	0.33	10	1.27	1647	<2	0.01	3	1747	183	1.22	<5	4	112	<5	<0.01	<10	<10	36	<10	266	2
122379	1.5	2.81	188	204	<0.5	8	6.86	7	18	12	22	6.44	<1	0.35	10	1.61	2461	<2	0.02	2	1493	171	2.09	<5	4	207	<5	<0.01	<10	<10	49	<10	211	3
122380	0.8	2.90	36	189	<0.5	7	4.83	2	18	9	18	5.70	<1	0.31	11	1.62	2103	<2	0.01	3	1766	39	0.51	<5	4	145	<5	0.01	<10	<10	48	<10	113	2
122381	1.0	2.91	51	221	<0.5	8	3.83	2	18	9	20	6.21	<1	0.34	10	1.61	1686	<2	0.01	3	1810	27	1.18	<5	4	121	<5	<0.01	<10	<10	46	<10	103	3
122382	1.4	2.58	174	237	<0.5	5	3.88	5	19	10	21	5.95	<1	0.31	<10	1.45	1704	<2	0.01	3	1740	31	1.54	<5	3	126	<5	0.02	<10	<10	44	<10	97	3
122382A	1.1	2.91	166	203	<0.5	<5	2.50	5	21	12	15	6.18	1	0.37	<10	1.67	1562	<2	0.02	4	1543	31	1.76	<5	5	81	<5	0.08	<10	10	58	<10	94	3
122383	1.4	2.47	144	201	<0.5	<5	3.01	5	21	9	33	5.96	1	0.34	<10	1.43	1427	<2	0.02	3	1728	97	1.95	<5	4	91	<5	0.07	<10	<10	48	<10	99	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.

Assayers Canada

8282 Sherbrooke St., Vancouver, B.C., V5X 4R6

Tel: (604) 327-3436 Fax: (604) 327-3423

Report No : **8V3699RJ**

Date : Nov-05-08

Ascot Resources Ltd

Attention: Sue Deane

Project: Dilworth/shipment 35

Sample type: Core

Multi-Element ICP-AES Analysis

Aqua Regia Digestion

Sample Number	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Sr ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm	Zr ppm
122384	3.1	2.37	265	193	<0.5	5	4.70	8	22	10	67	6.42	<1	0.37	<10	1.25	1734	<2	0.02	3	1656	126	3.10	<5	4	146	<5	0.05	<10	<10	45	<10	159	3
122385	0.7	3.33	18	177	<0.5	7	2.27	2	21	11	16	6.74	1	0.29	<10	1.77	1755	<2	0.02	3	1653	30	0.37	<5	5	77	<5	0.02	<10	<10	60	<10	118	3
122386	1.2	3.15	36	199	<0.5	9	3.66	2	22	9	27	6.56	<1	0.33	11	1.59	1952	<2	0.01	3	1702	94	0.64	<5	4	128	<5	0.01	<10	<10	48	<10	114	3
122387	0.7	3.10	18	209	<0.5	5	5.31	1	20	8	10	6.10	<1	0.31	10	1.74	2187	<2	0.01	3	1630	25	0.51	<5	5	172	<5	0.03	<10	<10	45	<10	91	3
122388	0.7	3.02	40	197	<0.5	8	5.14	2	21	8	15	6.18	1	0.33	10	1.64	2096	<2	0.02	3	1684	23	0.78	<5	4	156	<5	0.02	<10	<10	42	<10	95	3
122389	0.8	2.91	51	190	<0.5	8	4.31	2	21	9	18	6.18	<1	0.34	10	1.51	1909	<2	0.02	3	1719	23	0.92	<5	4	155	<5	0.01	<10	<10	46	<10	100	3
122390	0.6	2.88	11	243	<0.5	7	5.59	1	19	6	17	5.65	<1	0.40	11	1.50	1937	<2	0.02	3	1699	35	0.45	<5	4	225	<5	0.01	<10	<10	47	<10	128	3
122391	0.6	3.03	16	184	<0.5	7	5.42	1	20	7	17	6.10	<1	0.31	11	1.62	1947	<2	0.02	3	1749	24	0.40	<5	4	192	<5	0.01	<10	<10	49	<10	105	3
122392	2.1	2.30	94	181	<0.5	6	4.92	3	16	10	27	5.30	<1	0.33	<10	1.14	1966	<2	0.02	2	1533	58	1.44	<5	4	198	<5	0.01	<10	<10	42	<10	95	2
122393	21.1	2.36	86	181	<0.5	7	2.43	3	19	11	31	6.08	<1	0.34	10	1.20	1719	<2	0.02	3	1693	43	2.25	<5	3	81	<5	0.01	<10	<10	46	<10	137	3
122394	2.7	0.60	12	66	<0.5	6	14.63	1	4	72	8	1.35	<1	0.13	<10	0.29	4384	<2	0.01	1	448	<2	0.23	<5	2	1062	<5	<0.01	<10	<10	10	<10	21	<1
122395	3.1	2.01	312	140	<0.5	7	8.81	8	18	14	26	4.55	<1	0.27	<10	1.02	3104	<2	0.02	3	1211	26	1.34	<5	3	615	<5	<0.01	<10	<10	40	<10	74	1
122396	4.7	2.43	506	98	<0.5	9	3.19	16	33	13	52	7.68	<1	0.35	<10	1.52	1863	<2	0.03	5	1907	77	>5.00	<5	4	123	<5	0.01	<10	10	66	<10	346	4
122397	3.5	1.87	330	68	<0.5	9	4.51	12	31	27	54	7.23	<1	0.39	<10	1.08	1874	<2	0.03	6	1899	205	>5.00	<5	4	144	<5	0.01	<10	<10	47	<10	255	3
122398	8.3	1.18	344	164	<0.5	7	5.61	10	20	17	38	4.70	<1	0.33	<10	0.58	1875	<2	0.02	4	1214	58	3.87	<5	3	199	<5	0.01	<10	<10	31	<10	104	2
122399	11.7	1.68	1733	160	<0.5	8	7.27	46	25	31	64	6.56	<1	0.37	<10	0.99	2388	<2	0.03	4	1370	131	4.68	<5	4	237	<5	0.01	<10	13	45	<10	275	3
122400	<0.2	0.08	9	23	<0.5	12	>15.00	1	1	8	2	0.08	<1	0.03	<10	2.08	59	<2	0.01	<1	85	<2	0.06	<5	<1	4626	<5	<0.01	<10	12	2	<10	6	<1
122401	17.0	2.09	382	190	<0.5	5	6.26	12	25	20	55	5.80	<1	0.32	<10	1.30	2263	<2	0.03	3	1661	126	2.54	<5	5	176	<5	0.06	<10	<10	58	<10	387	3
122402	6.4	2.36	473	204	<0.5	6	5.18	13	24	11	59	5.82	<1	0.34	<10	1.33	1997	<2	0.04	3	1677	75	1.82	<5	5	146	<5	0.03	<10	12	68	<10	121	3
122403	2.9	2.57	128	208	<0.5	6	5.24	5	22	11	51	6.14	<1	0.26	<10	1.45	2028	<2	0.03	3	1517	124	1.48	<5	4	166	<5	0.02	<10	12	73	<10	205	3
122404	3.0	2.78	105	215	<0.5	7	5.15	4	25	11	54	6.67	<1	0.35	<10	1.83	2366	<2	0.03	3	1754	127	1.40	<5	5	154	<5	0.02	<10	12	90	<10	114	3
122405	2.1	2.16	194	215	<0.5	6	4.18	6	20	21	37	5.56	<1	0.34	<10	1.27	1648	<2	0.02	2	1534	53	1.44	<5	5	121	<5	0.01	<10	<10	59	<10	152	3
122406	3.3	2.62	226	249	<0.5	6	5.65	7	31	10	62	6.83	<1	0.42	<10	1.68	1994	<2	0.03	3	2027	100	2.43	<5	6	164	<5	0.04	<10	16	82	<10	139	3
122407	4.0	3.14	161	186	<0.5	<5	3.82	5	35	10	82	7.25	<1	0.31	<10	2.34	2420	<2	0.02	4	1839	57	1.14	<5	6	110	<5	0.07	<10	17	100	<10	179	3
122408	15.1	3.27	147	199	<0.5	8	4.04	7	39	9	99	7.63	<1	0.34	<10	2.31	2691	<2	0.03	7	1805	141	1.33	<5	6	128	<5	0.01	<10	17	112	<10	382	3
122409	3.1	3.02	118	178	<0.5	6	3.67	4	41	8	74	6.94	<1	0.30	<10	2.15	2787	2	0.03	8	1784	52	0.89	<5	5	113	<5	0.05	<10	17	91	<10	137	3
122410	4.1	2.84	94	242	<0.5	<5	2.45	3	36	9	73	6.40	<1	0.40	<10	1.89	2590	<2	0.03	8	2071	55	0.83	<5	5	76	<5	0.07	<10	<10	82	<10	132	3

A .5 gm sample is digested with 5 ml 3:1 HCl/HNO3 at 95°C for 2 hours and diluted to 25ml.